

Norex Development Ltd.

PIK 1-6 Y56257-62

4-Mile Creek, 20 miles E of Mayo, Yukon.

63° 35' N  
135° 12' W            105-M-11

by

B. Fitch (?)

061283

N.M.E.A.P.

Received Jan. 9, 1976

ANTIMONY PROSPECT ON PIK CLAIMS

EXPLANATION OF SKETCHES


SKETCH I shows the location of the main vein in relation to the Pik claims and assay results from samples taken prior to 1975.

SKETCH II shows the location of chip samples taken in 1975 on the mineralized veins. Samples 1 to 9 were taken along the vein for five foot intervals. Samples 10, 11 ( 25 ft. west of #13 ), 13, and 14 were taken across the mineralized veins.


SKETCH III shows the soil sampling results and local geology from the area surrounding the mineralized veins.

TABLE OF ASSAYS and ore values is based on the results of the chip sampling (SKETCH II) and current smelter purchasing prices.

SKETCH I



SKETCH II



SKETCH III




KEY

- x surface soil sample (ppm)
- o soil sample near bedrock
- outcropping
- /— trenching

0                      100

1 in. = 100 ft.

50°



CAMP



CREEK BED




TABLE OF ASSAYS AND ORE VALUES OVER MINING WIDTHS

Sample Number	Assay Percent Sb	Average Thickness	Percentage Over <sup>5.?</sup> (4) feet	Pounds per ton	Value per ton ( 75 ¢ lb.)
1.	19.25	4 in	1.6	32	\$ 24.00
2.	42	6 in	5.25	105	78.25
3.	48	7 in	7	140	105.00
4.	22.5	4 in	1.8	36	27.00
5.	6.5	2 in	.52	10.4	7.80
6.	3.16	3 in	.2	4	3.00
7.	20.25	10 in	4.2	84	63.00
8.	64.5	13 in	17.4	348	261.00
9.	70.5	8 in	11.8	236	177.00
-----					
10.	44	18 in	16.5	330	247.50
11.	2.64	10 ft	2.64	53.8	40.35
13.	39	2 ft	19.5	390	292.50
14.	49.8	1 ft	12.45	249	186.75

Average value of vein along 45 feet ( samples 1 - 9 ) averages \$ 82.95 per ton. No allowance is made for mineralization in foot and hanging walls.

DATE. July 31, 1975

FILE NO. 9117 - 11

# ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.  
BOX 4518 WHITEHORSE Y. T.  
PHONE 667 2694 Y1A 2R8  
(B. FITCH)

SAMPLE RECEIVED FROM

NOREX DEVELOPMENT

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz Per Ton	ANTIMONY (lb) Percent				
#1			19.25				
#2			42.00				
#3			48.00				
#4			22.50				
#5			6.50				
#6			3.16				
#7			20.25				
#8			64.5				
#9			70.5				
#10			44.00				
#11			2.64				
Lot # A-816							
S-1			.18				
S-2			7.40				

ASSAYER.

*H. Heyland for*



# ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.  
BOX 4518 WHITEHORSE Y. T.  
PHONE 667 2694 Y1A 2R8

DM

NOREX DEVELOPMENT ( B. FITCH )

SAMPLE #

12

13

14

15

16

SILVER Oz Per Ton	ANTIMONY					
	.61					
	39.0					
	49.8					
	.46					
	.07					

ASSAYER.

*K. Hayward*

GEO. CHALMERS



WHITEHORSE ASSAY OFFICE  
 BOX ~~312~~ 1513  
 WHITEHORSE, YUKON

Samples from: NORDEX DEVELOPMENT

Lot. No.: A-516-29

*All Results - P. 111*

	SAMPLE #	Sb					
L-O	0+00 NW	TR					
	1+00 N	TR					
	2+00 NW	TR					
	3 NW	TR					
	4 NW	TR					
	5 NW	TR					
L-O	6 NW	TR					
L2NE	1 NW	TR					
	2 NW	4					
	3 NW	4					
	4 NW	1					
	5 NW	TR					
L2NE	6 NW	4					
L2SW	0 NW	184 *					
	1 NW	4					
	2 NW	TR					
	3 NW	4					
	4 NW	4					
	5 NW	TR					
L2SW	6 NW	TR					
L4SW	0 NW	TR					
	1 NW	TR					
	2 NW	4					
	3 NW	2					
	4 NW	TR					
	5 NW	8					
L1W	6 NW	TR					
	S-1	WET ASSAY - TOO HIGH FOR GRADUATION					
	S-2	WET ASSAY - TOO HIGH FOR GRADUATION					



DATE. NOVEMBER 22, 1975.

FILE NO. A-877-9



# ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.  
BOX 4518 WHITEHORSE Y. T.  
PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM

NOREX DEVELOPMENTS

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	ANTIMONY PPM				
C-1			64				
C-2			8				
C-3			16				
C-4			24				
C-5			32				
C-6			8				
C-7			8				
C-8			8				
C-9			8				

ASSAYER. glt