

091305

GOLDEN GATE EXPLORATION LTD.

PROPERTY: Rex Asbestos BEARING: 050° DATE COLLARED: June 4, 1966
 HOLE NO.: S-1 DIP: -45°
 LOCATION: Rex 1 M.C. ELEVATION: 2790.0' COMPLETED: June 10, 1966

FROM	TO	DESCRIPTION
0.0	16.0	Overburden.
16.0	45.0	Medium grained peridotite with occasional black threads and ribbons of aphenitic rock chiefly at 45° to core.
45.0	65.0	Serpentinized peridotite with occasional slip fibre.
65.0	442.5	Serpentinization increasing with irregular threads and ribbons of chrysotile.

FROM TO FIBRE MEASUREMENT BY J. W. McCARTHY


FROM	TO	1/16	1/8	3/16	1/4	5/16	3/8	7/16	1/2	1/2+	Total	L	%
63.0	68.0												
68.0	73.0										6	30°	0.6
73.0	83.0												
83.0	88.0		2								8	45	0.8
88.0	93.0												
93.0	98.0	1									1	45	0.1
98.0	103.0	1	8								9	40	0.9
103.0	108.0	1									1	30	0.1
108.0	113.0	2	2	3	4						11	60	1.1
113.0	118.0												
118.0	123.0		4								4	40	0.4
123.0	128.0	6	6	6							18	45	1.8
128.0	133.0	2									2	45	0.2
133.0	138.0												
138.0	143.0	1	2	3				7			13	60	1.3
143.0	148.0												
148.0	153.0		2								2	15	0.2
153.0	158.0							7			7	30	0.7
158.0	163.0	3			4						7	30	0.7
163.0	168.0		3								3	75	0.3
168.0	173.0	4	4		8						16	30	1.6
173.0	178.0	1	2	6							9	30	0.9
178.0	183.0	3	4	6		5					18	60	1.8
183.0	188.0	3	2	3	8						16	40	1.6
188.0	193.0	5	2	6							13	50	1.3
193.0	198.0	5	4								9	45	0.9
198.0	203.0			3							3	75	0.3
203.0	208.0	2	2	3							7	45	0.7
208.0	213.0	3	2								5	60	0.5
213.0	218.0	1	4								5	30	0.5
218.0	223.0	4	8	6	8						26	30	2.6
223.0	228.0	1			16						17	45	
228.0	233.0	1	8	6	8		6				29	45	2.9



GOLDEN GATE EXPLORATION LTD.

DDH No. S-1 (Cont'd)

FROM TO		DESCRIPTION												
FROM TO		FIBRE MEASUREMENT BY J. W. McCARTHY												
		1/16	1/8	3/16	1/4	5/16	3/8	7/16	1/2	1/2+	Total	L	%	
233.0	238.0	4	8	3	4						19	60	1.9	
238.0	243.0	1	2	9	8						20	70	2.0	
243.0	248.0	7	18	3	12						40	60	4.0	
248.0	253.0	10	8	21	8	5					52	45	5.2	
253.0	258.0	9		3	4	5					21	45	2.1	
258.0	263.0	5	12	6	4						27	45	2.7	
263.0	268.0	1	6		4	5					16	45	1.6	
268.0	273.0	5		6	4						15	60	1.5	
273.0	278.0	3	4								7	60	0.7	
278.0	283.0	1									1	45	0.1	
283.0	288.0	1	6								7	45	0.7	
288.3	293.0		2	6	4						12	30	1.2	
293.0	298.0		6	3					8		17	30	1.7	
298.0	303.0	6	4	3	8	5					26	45	2.6	
303.0	308.0	4	2	3	8	5					22	30	2.2	
308.0	313.0	5				5					10	50	1.0	
313.0	318.0	1	2	3							6	50	0.6	
318.0	323.0	2		3							5	45	0.5	
323.0	328.0													
328.0	333.0	8					6				14	45	1.4	
333.0	338.0	3	2	3							8	60	0.8	
338.0	343.0	7									7	45	0.7	
343.0	348.0	1	2	6		5					14	60	1.4	
348.0	353.0	1	2		4	5				10	22	50	2.2	
353.0	358.0	1	2								3	70	0.3	
358.0	363.0	3	4								7	60	0.7	
363.0	368.0													
368.0	373.0	1	4		4						9	60	0.9	
373.0	378.0		2		4						6	45	0.6	
378.0	388.0													
388.0	393.0	1	2	3						10	16	45	1.6	
393.0	398.0													
398.0	403.0					5					5	70	0.5	
403.0	408.0	2	2	6				7			17	60	1.7	
408.0	413.0		2								2	75	0.2	
413.0	418.0	2									2	30	0.2	
418.0	442.5													



442.5 472.0 Dark and light grey breccia with minor indications of fibre
 472.0 495.0 Chiefly greenstone
 495.0 500.0 Appears to be kaolinized diorite (?)

500.0' is the end of the hole.
 Fibre measurement conservative.

Jos. Sullivan
 Jos. Sullivan
 August 20, 1966

GOLDEN GATE EXPLORATION LTD.

PROPERTY: Rex Asbestos BEARING: 050° DATE COLLARED: June 10, 1966
 HOLE NO.: S-2 DIP: -60° COMPLETED: June 14, 1966
 LOCATION: Rex 1 M.C. ELEVATION: 2790'
 FROM TO DESCRIPTION

0.0 13.0 Overburden
 13.0 78.0 Medium grained unaltered peridotite
 78.0 341.0 Serpentinized peridotite with irregular threads and ribbons of chrysotile

FROM TO FIBRE MEASUREMENT BY J. W. McCARTHY

FROM	TO	1/16	1/8	3/16	1/4	5/16	3/8	7/16	1/2	1/2+	Total	L	%
78.0	83.0		2								2	80°	0.2
83.0	93.0					Nil Reported							
93.0	98.0	1									1	45	0.1
98.0	103.0	1									1	70	0.1
103.0	108.0	1									1	45	0.1
108.0	113.0					Nil Reported							
113.0	118.0	3	4								7	70	0.7
118.0	133.0					Nil Reported							
133.0	138.0		2		4	5					11	10	1.1
138.0	153.0					Nil Reported							
153.0	158.0	1		3							4	60	0.4
158.0	163.0					Nil Reported							
163.0	168.0	2									2	60	0.2
168.0	173.0	1	2								3	70	0.3
173.0	193.0					Nil Reported							
193.0	198.0		2								2	80	0.2
198.0	203.0		2								2	80	0.2
203.0	208.0	1									1	45	0.1
208.0	213.0	1									1	80	0.1
213.0	218.0	3	4	3							10	70	1.0
218.0	223.0					Nil Reported							
223.0	228.0		2								2	30	0.2
228.0	233.0	2									2	20	0.2
233.0	238.0	1	2								3	70	0.3
238.0	243.0	4									4	60	0.4
243.0	248.0	2						7			9	60	0.9
248.0	253.0			3		5					8	60	0.8
253.0	258.0	1	4	3	4						12	60	1.2
258.0	263.0	2	2	6			6				16	60	1.6
263.0	268.0					Nil Reported							
268.0	273.0	1									1	70	0.1
273.0	293.0					Nil Reported							
293.0	298.0		2								2	20	0.2
298.0	333.0					Nil Reported							
333.0	338.0		2		4						6	60	0.6
338.0	341.0					Nil Reported							



341.0' is the end of the hole.
 Fibre measurement conservative.

Joe Sullivan
 Joe Sullivan
 August 20, 1966

106-2-4

091305

GOLDEN GATE EXPLORATION LTD.

PROPERTY: Rex Asbestos BEARING: 050° DATE COLLARED: June 25, 1966
 HOLE NO.: S-5 DIP: -45° COMPLETED: July 6, 1966
 LOCATION: REX No. 2 M.C. ELEVATION: 2790.0*

FROM	TO	DESCRIPTION
0.0	18.0	Overburden
18.0	92.0	Relatively fresh peridotite, minor chrysotile
92.0	399.0	Serpentinized peridotite with gradually increasing chrysotile fibre

FROM		TO		FIBRE MEASUREMENT (J. W. McCarthy)											
				1/16	1/8	3/16	1/4	5/16	3/8	7/16	1/2	1/2+	Total	L	%
53.0	58.0					3							3	45	0.3
58.0	63.0		2										2	60	0.2
63.0	83.0						Nil Recorded						4	0	0.4
83.0	88.0						4						4	0	0.4
88.0	93.0						Nil Recorded						4	60	0.4
93.0	98.0	2	2										4	60	0.4
98.0	103.0						Nil Recorded						3	45	0.3
103.0	108.0	3											2	50	0.2
108.0	113.0	2					Nil Recorded						2	50	0.2
113.0	128.0						Nil Recorded						1	0	0.1
128.0	133.0	1											1	60	0.1
133.0	138.0	1											1	60	0.1
138.0	143.0		2										2	45	0.2
143.0	148.0	3											3	60	0.3
148.0	153.0	1				3							4	60	0.4
153.0	158.0						Nil Recorded						4	60	0.4
158.0	163.0	4											4	60	0.4
163.0	168.0	1	2		3								6	45	0.6
168.0	173.0	1			3	4	5	12	7				32	60	3.2
173.0	178.0	2	4		3	4		6		8			27	50	2.7
178.0	183.0	1			12	4	10	6				11	44	45	4.4
183.0	188.0	5	10		3								18	30	1.8
188.0	193.0	1				4							5	10	0.5
193.0	198.0		2						7				9	0	0.9
198.0	203.0	1	2			4							7	45	0.7
203.0	208.0		4										4	60	0.4
208.0	213.0				3								3	90	0.3
213.0	218.0		2		3								5	60	0.5
218.0	223.0							6					6	20	0.6
223.0	228.0		2		3								5	45	0.5
228.0	233.0	4	4										8	70	0.8
233.0	238.0		2										2	60	0.2
		4	4										8	45	0.8
243.0	248.0	4	4										8	45	0.8
248.0	258.0						Nil Recorded						8	45	0.8
258.0	263.0		2		3								5	20	0.5
263.0	268.0	2	2										4	20	0.4
268.0	273.0	1	2		3	4							10	60	1.0
273.0	278.0	2	6		3								11	45	1.1

GOLDEN GATE EXPLORATION

DIAMOND DRILL RECORD

PROPERTY: REX ASBESTOS	BEARING: 050°	DATE COLLARED:	LOGGED BY:
HOLE NO. S-5	DIP: -45°	COMPLETED:	J. Sullivan
LOCATION: REX No. 2 M.C.	ELEVATION: 2790.0'		

FROM	TO	DESCRIPTION	FROM	TO	SAMPLING	FROM	TO	REC.
0.0	18.0	Overburden						
18.0'	92.0'	Relatively fresh peridotite						
92.0'		Serpentinized peridotite 92.0' - 100.0' = 1% fiber, 1/10" fiber length 100.0' - 110.0' = 1% fiber 110.0' - 120.0' = 1.5% fiber, 1/10" fiber length 120.0' - 130.0' = 1% fiber 130.0' - 140.0' = 1.5% fiber 140.0' - 150.0' = 1% of 1/10" fiber 150.0' - 160.0' = 1% fiber 157.0' - 159.0' = fresh breccia, chiefly talc 160.0' - 170.0' = 2% fiber, much lost core, possibly a better grade 170.0' - 180.0' = up to 10% fiber, fiber length as high as 1/2" 180.0' - 190.0' = 2.5% fiber 190.0' - 200.0' = +5% fiber, chiefly at 195.0' 193.0' - 194.0' = mainly talc 200.0' - 204.0' = 30% lost core, appears to be travelling down the break, excellent chryostile <u>hole is continuing</u> June 29, 19:00 hrs. bottom of hole at <u>287.0'</u>						