

**ASSESSMENT REPORT ON THE
SILVER HART PROPERTY
2005 DRILLING PROGRAM**

**Watson Lake Mining District
Work Completed: September 11- October 3, 2005**

CLAIMS:	CMC 1-24	YA56628 – YA56651
	CMC 25-38	YA70616 – YA70629
	CMC 39-41	YA70708 – YA70710
	CMC 43-104	YA70712 – YA70773
	G. L. 1-2	YA99544 – YA99545
	G. L. 3-10	YA99548 – YA99555
	G. L. 11	YA99559
	G. L. 12-13	YA99546 – YA99547

LOCATION: 1. 160 kilometers west of Watson Lake, Yukon
2. NTS Map Area 105B-07
3. Latitude: 60°19'N by Longitude: 130 °45'W

FOR: CMC METALS LTD
856 HOMER STREET, SUITE 207
VANCOUVER, BC
V6B 2W5

BY: R. Allan Doherty, B.Sc., P. Geo.
Aurum Geological Consultants Inc.
106A Granite Road
Whitehorse, Yukon
Y1A 2V9

April 21, 2005

TABLE OF CONTENTS

1. SUMMARY	1
2. INTRODUCTION AND TERMS OF REFERENCE	2
3. DISCLAIMER	2
4. PROPERTY DESCRIPTION AND LOCATION	2
5. ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSOGRAPHY	6
6. HISTORY	6
7. GEOLOGICAL SETTING	7
7.1 REGIONAL GEOLOGY	7
7.2 PROPERTY GEOLOGY	7
8. DEPOSIT TYPES	7
9. MINERALIZATION	8
10. EXPLORATION	8
11. DRILLING	8
FIGURE 3	9
12. SAMPLING METHOD AND APPROACH	10
12.2 QUALITY CONTROL	10
13. DATA VERIFICATION	10
14. ADJACENT PROPERTIES	11
15. INTERPRETATION AND CONCLUSIONS	11
16. REFERENCES	11
17. CERTIFICATE OF QUALIFICATIONS	12
18. STATEMENT OF COSTS	14

LIST OF FIGURES

Figure 1. Property Location Map	3
Figure 2. Claim Map	5
Figure3. Drill Hole Location Map	9

LIST OF TABLES

TABLE I. CMC SILVER Property - Claim Status	4
--	---

LIST OF APPENDICIES

APPENDIX A: Drill Hole Logs and Assay Logs	15
---	----

1. SUMMARY

The CMC Silver property is located in south-central Yukon Territory, 160 kilometers west of Watson Lake, Yukon (Figure 1). The property includes 116 un-surveyed continuous claims covering an area of approximately 2,017 hectares.

There is no record of production from the general property area; however it has seen a long history of staking and exploration activity over the past century. Underground development on the vein system was completed in 1984-85 and consisted of a 673 m adit and two rises. During the same period, a 40 km access road was built from the Alaska Highway to the property.

The CMC Silver property was acquired by Bellevue Capital Corp in 2004 and subsequently transferred to CMC Metals Corp, who performed the 2005 work program.

Results from the drilling program confirm that there is a continuous system of narrow but very high grade (up to 5000 gm/t Ag) silver veins which also report lead, zinc, and minor copper and gold. Previous work has traced the zone of veining for some 1,160 m. The 2005 drill program consisted of 14 drill hole (702.19 m) over a strike length of some 2000 m on the vein system.

Continued exploration is warranted and recommended on the CMC Silver property.

2. INTRODUCTION AND TERMS OF REFERENCE

This report was prepared at the request of Mr. Don Wedman, President of CMC Metals Ltd. Its purpose is to comply with the reporting requirements under the “Schedule of Representation” guidelines and the Yukon Quartz Mining Act. This report also serves to satisfy the standards of disclosure for mineral projects under National Instrument 43-101 through a description of previous exploration work carried out on the claims. On September 18, the author visited the project site and inspected a number of the showings on the property accompanied by Ryan Grywal project geologist, employed by Dahrouge Geological Consultants who supervised the exploration work on site. At the time of the visit, drilling, sampling and QA/QC procedures were reviewed.


3. DISCLAIMER

Although soil and rock analytical data, derived from previous reports has been reviewed, the author assumes no responsibility for the validity of analytical results other than those collected under his supervision in 2005. In reviewing, referencing and reporting on property data, the author has not, to his knowledge, relied on the opinion or statement of other experts who are not qualified persons.

The author has made no attempt to verify the legal status and ownership of the CMC Silver property claims, nor is he qualified to do so. The information regarding property title and ownership was obtained from the Yukon Government claim titles web site. The author saw no evidence to suggest that it is not correct.

4. PROPERTY DESCRIPTION AND LOCATION

The CMC Silver property is rectangular block of 116 claims trending SW-NE located within NTS map area 105 B-07 in the Cassiar Mountains. The claims are accessible by a 41 km gravel road that leaves the Alaska Highway at Kilometer 1116 approximately 2 km west of the Continental Divide Restaurant and gas station. The road follows a chain of lakes to Edgar Lake where it climbs steeply to the alpine and the location of the exploration camp and old workings. Property location is shown in Figure 1, and Table I lists all claims included in the property with their requested expiry date.



**Figure 1 - Location Map
CMC Silver Property**


TABLE 1. CMC SILVER PROPERTY CLAIM STATUS

Claim Name	Claim #	Number of Claims	Grant/Record Number.	Operation Recording Date m/d/yr	Claim Expiry Date m/d/yr
CMC	1-24	24	YA56628-YA56651	03/05/2004	03/05/2010
CMC	25-38	14	YA70616-YA70629	03/05/2004	03/05/2007
CMC	39-41	3	YA70708-YA70710	03/05/2004	03/05/2010
CMC	43-104	62	YA70712-YA70773	03/05/2004	03/05/2007
G. L.	1-2	2	YA99544-YA99545	03/05/2004	03/05/2010
G.L.	3-11	9	YA99548-YA99557	03/05/2004	03/05/2010
G.L.	12-13	2	YA 99546-YA99547	03/05/2004	03/05/2010
Total Claims		116			

Above information obtained from the Yukon Government, Department of Energy Mines and Resources web site. Expiry dates are subject to acceptance of an assessment report by the Watson Lake Mining Recorder.

In accordance with the Yukon Quartz Mining Act, yearly extensions to the expiry dates of quartz claims are dependent upon conducting \$100 of work per claim or paying the equivalent cash in lieu of work. Work must be filed in the year the work was completed. Excess work can be used to extend expiry dates up to maximum of four years. Assessment costs can be applied to adjoining claims through filing grouping certificates. Filing a statement of work and costs and submission of an assessment report to the Watson Lake Mining Recorder verifying completion of the work, are also required no later than six months after the anniversary date of the claim.

The claims are located within the traditional territory of the Liard First Nation. The Liard First Nation has not settled its land claim agreement however they are generally supportive of mining developments. On the northeast side of the CMC claim block is a large block of withdrawn land noted on claim maps as LFN R-147B. The southwest side of this large withdrawn area follows the Meister River.



5. ACCESSIBILITY, CLIMATE, LOCAL RESOURCES, INFRASTRUCTURE AND PHYSOGRAPHY

The most immediate and direct access to the CMC Silver property is via the Alaska Highway to Kilometer 116 and from there by gravel road for 41 km to the property. Access is limited to the snow free months of the year.

The climate in southeastern Yukon is typically semi-arid; summers are warm with frequent afternoon showers and thunderstorms. An interior continental climate with precipitation of about 31 cm annually, warm summers and cold winters typifies the area. Permafrost is common, especially on the steeper north and east facing slopes and lower forested areas. Most of the property is above the tree line. Ground cover consists of sparse alpine fir, spruce, alder, dwarf willow and birch.

The Town of Watson Lake (population 350) is the closest centre for obtaining groceries, fuel, accommodation and some limited rental and contracted exploration services. Trans North Helicopters maintains a summer helicopter base in Watson Lake.

The exploration season in this part of the Yukon normally extends from late May to late September but cool rainy conditions and snow-storms are not uncommon in late August and September. The months of June through September are normally free of snow cover.

6. HISTORY

The CMC Silver property area has seen intermittent exploration activity since the 1920's. The first recorded claims were staked in August 1948 by Great Northern Exploration Company Ltd. No records of early work have been found. The claims were re-staked in 1971 by the Wolf Lake Joint Venture who carried out grid soil sampling and detailed geological mapping in 1972.

The claims were re-staked as CMC 1-24 by A. W. Hyde, a prospector from Whitehorse. The claims were subsequently optioned to BRX Mining and Petroleum Corp in 1982. Exploration efforts consisted of geological mapping and geochemical sampling and 2 diamond drill holes (197 m); additional claims were added to the west. The option was terminated later that year and Hyde and T. McCrory and B. Preston completed additional trenching in 1983 and optioned the claims to United Greenwood Exploration Ltd. And Consolidated Montclerg Mines in late 1983. Apparently no work was undertaken and the option was terminated.

In late 1984 the property was optioned to Silver Hart Mines Ltd., and Shakwak Exploration Company Ltd. Work consisted of additional claim staking, 50 diamond drill holes (3,658 m) driving a 673 m adit and two raises on the vein system. At this time a 41 km road was constructed to the property.

7. GEOLOGICAL SETTING

7.1 REGIONAL GEOLOGY

The CMC Silver property is located in the Ominica belt of the western Canadian Cordillera. The area is known as the Rancheria silver district as a number of silver vein and skarn occurrences have been located and extensively worked in the area.

The Cretaceous Cassiar Batholith is a large batholith that extends along this portion of the Ominica Belt and hosts numerous silver lead zinc occurrences within the Rancheria district. The intrusion is a complex polyphase intrusion and includes medium to coarse grained, equigranular to porphyritic (K-feldspar) granite and biotite quartz monzonite; biotite-hornblende quartz monzonite and granodiorite. The Cassiar Batholith intrudes Lower Cambrian sedimentary and metamorphic rocks.

The main formations in the area are the Rosella Formation consisting of resistant, thick bedded to massive, limestone and argillaceous limestone; local archaeocyathid buildups, trilobite fragments, oolites, and pisolites; pisolitic massive dolomite and limestone; marble, calc-silicate, calcareous phyllite and minor schist.

The Boya Formation consisting of light grey to medium brown, fine to medium grained quartz arenite and interbedded argillite, slate, siltstone, phyllite and minor limestone

7.2 Property Geology

The geology of the CMC Silver property comprises the contact zone of the Cretaceous Cassiar Batholith with Lower Cambrian Boya Formation. The sediments are primarily interbedded quartz rich clastic rocks with derived schists and gneisses. The contact of the intrusion trends northwesterly with the intrusive to the west and the sediments to the east. Although some of the contacts are intrusive and contain small skarn zones in calcareous horizons, many of the contacts are believed to be faulted, Read (1987).

Vein systems have a 045° strike with steep east dips. The veins consist of a wide shear zone containing lenses of galena, tetrahedrite and sphalerite mineralization. Three mineralized zones about 1.8 m wide named the TM, FM, & SM have been traced over 1,160 m.

8. DEPOSIT TYPES

The current deposit type being explored for on the CMC Silver property is polymetallic veins containing galena, tetrahedrite and sphalerite. The veins are best described as classic metasediment- hosted silver-lead-zinc veins, or silver /base metal epithermal veins. This type of mineralization is described in Yukon Mineral Deposit Profiles # I05.

9. MINERALIZATION

Mineralization on the CMC property consists of silver rich veins containing galena, tetrahedrite and sphalerite. Geochemical assays and analyses report high grade silver 100-5000 gm/t Ag, lead to a few percent lead and zinc and traces of copper and gold.

10. EXPLORATION

During 2005 CMC Metals Ltd. conducted diamond drilling on the established vein systems. The drilling work was contracted to DJ Drilling Ltd of Watson Lake. The crew was mobilized to the property by truck from Whitehorse and the drill was mobilized from Watson Lake. The old camp buildings and tents were used to accommodate the crew.

11. DRILLING

The 2005 drilling program on the CMC claims was completed between September 11th and October 3, 2005. A total of 14 drill holes (702.19 m) were completed on the silver veins.

Significant intercepts from the drilling program are listed below and complete drill logs and assay logs are provided in Appendix A. All drill cores are stored on the property.

Drill Hole	From (m)	To (m)	Interval (m)	Lead %	Zinc %	Silver (gm/T)
DH05-01	30.13	30.21	0.08	53.14	0.12	5886
DH05-02	22.12	23.92	1.8	0.19	8.32	1826
DH05-02	38.11	38.61	0.5	0.48	5.75	238
DH05-03	22.30	22.75	0.45	12.61	1.77	1663
DH05-04	3.05	5.15	2.1	0.01	4.04	5
DH05-04	18.00	22.5	4.5	0.24	3.74	42
DH05-04	52.44	54.6	2.16	0.08	2.5	69
DH05-05	19.43	20.42	0.99	0.11	3.96	8
DH05-05	36.10	38.1	2	0.02	4.42	1
DH05-07	3.20	25.9	22.7	0.17	4.63	76
DH05-08	23.00	25.45	2.45	4.21	3.12	899
DH05-09	7.50	23.95	16.45	0.12	2.85	133
DH05-10	12.20	13.2	1	0.17	0.15	165
DH05-11	27.75	28	0.25	0.03	6.3	1474
DH05-12	14.45	15.9	1.45	0.23	34.62	1716
DH05-13	1.23	1.92	0.69	8.76	1.95	4830
DH05-14	16.30	17.3	1	0.08	0.15	211
DH05-14	23.35	23.5	0.15	4.81	44.26	2654

FIGURE 3




FIGURE 3

CMC Metals Ltd.

DAHROUGE GEOLOGICAL CONSULTING LTD.
EDMONTON, ALBERTA

CMC Property, South Central, Yukon

**2005 Trench
And Diamond Drillhole
Locations**

RG 2005.10

12. SAMPLING METHOD AND APPROACH

Core samples were collected from drill holes on the CMC Claims during the 2005 drilling program. All zones of veining were sampled, and sections of wall rock from the footwall and hanging wall were also sampled. A total of 483 samples including blanks and standards were submitted for assay (Au and Ag gm/t) and 22 element ICP analyses.

12.2 Quality Control

Quality control procedures on core samples consisted of standardized rock sampling techniques. Blind duplicates and commercial standard samples were included for approximately each batch of 15 samples. Analytical work was completed by ACME Analytical Laboratories Ltd. in Vancouver. Sample analyses were by acid digestion and analyses by ICP-ES method and fire assay for Ag and Au.

13. DATA VERIFICATION

The author has reviewed all previous reports on the property. Most of the previous work on the property was completed prior to 2001, and the effective date of NI 43-101. There was no QA/QC of sampling methodology discussed in any geological report that the author reviewed.

The author has no reason to believe that the data as presented is not an accurate representation of facts at this early stage of exploration on the CMC Silver property.

14. ADJACENT PROPERTIES

There are contiguous mineral claims on the south side of the CMC Property staked by Archer Cathro and Associates (1981) Ltd. Yukon Minfile 105B020 describes this mineral occurrence as a drilled prospect containing W-skarn with major commodities listed as lead, zinc, and silver and minor commodities listed as copper, tungsten and gold.

15. INTERPRETATION AND CONCLUSIONS

The 2005 diamond drill program on the CMC property was successful in confirming high grade silver vein systems on the property.

**Respectfully submitted,
April 20, 2005**

R. Allan Doherty, P. Geo.

16. REFERENCES

Read, W. S. And J. A. McCrea, 2005. Technical Report On The Cmc Silver Property, Edgar Lake, Yukon Territory. Prepared For Bellevue Capital Corp

Deklerk , R. And Traynor, S. (Compilers), 2005. Yukon Minfile 2005. Yukon Geological Survey, Cd-Rom.

17. CERTIFICATE OF QUALIFICATIONS

I, R. Allan Doherty, hereby certify that:

1. I am a consulting mineral exploration geologist with Aurum Geological Consultants Inc., 106a Granite Road, Whitehorse, Yukon, Y1A 2V9.
2. I am a graduate of the University of New Brunswick, with a degree in geology (Hons. B.Sc., 1977). I attended graduate school at Memorial University of Newfoundland, 1978-80. I have been involved in geological mapping and mineral exploration primarily in the Yukon continuously since 1980.
3. I am a "Qualified Person" as defined in sec 1.2 of National Instrument 43-101.
4. I am a member in good standing of the Association of Professional Engineers and Geoscientists of the Province of British Columbia, registration no. 20564, and have been registered as a professional geologist since 1993.
5. I am author of this assessment report on the CMC claims. The report is based on a literature review and on private company reports and on property visit on September 18, 2005. Work was conducted from September 11-October 3, 2005.
6. I am the author of all sections of this report.
7. I am not aware of any material fact or material change with respect to the subject matter of this technical report, which is not reflected in the technical report, the omission to disclose makes the technical report misleading.
8. I am independent of the issuer and have no direct or indirect interest in the properties or securities of CMC Metals Ltd., or affiliated companies, nor do I expect to receive any.
9. I have had direct involvement with the exploration programs conducted on the area discussed in this report for CMC Metals Ltd..
10. I have read National Instrument 43-101 and form 43-101f and have prepared this technical report on the CMC claims in compliance with this instrument and form 43-101f1.
- 11.

R. Allan Doherty, P. GEO.

April 20, 2006

18. STATEMENT OF COSTS

CLAIMS:

CMC 1-24 YA56628 – YA56651
CMC 25-38 YA70616 – YA70629
CMC 39-41 YA70708 – YA70710
CMC 43-104 YA70712 – YA70773
G. L. 1-2 YA99544 – YA99545
G. L. 3-10 YA99548 – YA99555
G. L. 11 YA99559
G. L. 12-13 YA99546 – YA99547

Assessment costs of \$ 58,000 required for 580 claim years renewed.

All work completed between September 11- October 3, 2005

Diamond Drilling Costs:

Drill Hole #	Metres	Cost	Claim #
2005-01	58.56	\$ 6,734.40	CMC 28
2005-02	39.81	\$ 4,578.15	CMC 28
2005-03	44.60	\$ 5,129.00	CMC 28
Subtotal-	142.97	\$ 16,441.55	CMC 28
2005-04	57.25	\$ 6,583.75	CMC 27
2005-05	51.20	\$ 5,888.00	CMC 27
2005-06	38.10	\$ 4,381.50	CMC 27
Subtotal-	146.55	\$ 16,853.25	CMC 27
2005-07	45.10	\$ 5,186.50	CMC 11
2005-08	52.70	\$ 6,060.50	CMC 11
2005-09	43.60	\$ 5,014.00	CMC 11
Subtotal-	141.40	\$ 16,261.00	CMC 11
2005-10	45.10	\$ 5,186.50	CMC 28
2005-11	33.90	\$ 3,898.50	CMC 28
2005-12	67.40	\$ 7,751.00	CMC 28
2005-13	10.10	\$ 1,161.50	CMC 28
2005-14	69.50	\$ 7,992.50	CMC 28
Subtotal-	226.00	\$ 25,990.00	CMC 28
Total-	656.92	\$ 75,545.80	

Total Direct drilling costs \$75,545.80

R. Allan Doherty, P.Geo 2.0 days @ \$ 500/day \$ 1,000.00

Ryan Grywal Geologist 23 days @ \$300/day \$ 6,900.00

Clinton Davies Geologist 23 days @ \$250/day	\$ 5,750.00
--	-------------

Expenses

483 Core Sample Analyses/Assays @ \$20 per sample	\$ 9,960.00
---	-------------

Camp costs (138 man days @ \$75/day)	\$10,350.00
--------------------------------------	-------------

Total Eligible Assessment costs	\$109,505.80
--	---------------------

APPENDIX A

**DRILL CORE LOGS AND ASSAY LOGS
Holes DH05-01 to DH05-14**

Drill Hole	From (m)	To (m)	Interval (m)	Lithology
CMC 05-01	0	1.52	1.52	Casing
CMC 05-01	1.52	30.83	29.31	Granodiorite
CMC 05-01	30.83	52.9	22.07	Granodiorite
CMC 05-01	52.9	64.94	12.04	Granodiorite
CMC 05-02	0	2.13	2.13	Casing
CMC 05-02	2.13	59.45	57.32	Granodiorite
CMC 05-03	0	3.05	3.05	Casing
CMC 05-03	3.05	49.1	46.05	Granodiorite
CMC 05-04	0	3.05	3.05	Casing
CMC 05-04	3.05	5.15	2.1	Schist?
CMC 05-04	5.15	10.3	5.15	Dolostone
CMC 05-04	10.3	17.1	6.8	Granodiorite
CMC 05-04	17.1	25.2	8.1	?MnO ₂ ? (Sch?)
CMC 05-04	25.2	33.5	8.3	Dolostone
CMC 05-04	33.5	35	1.5	Granodiorite
CMC 05-04	35	36.9	1.9	Schist
CMC 05-04	36.9	60.2	23.3	Dolostone
CMC 05-04	60.2	62.6	2.4	Skarn
CMC 05-05	0	4.57	4.57	Casing
CMC 05-05	4.57	12.5	7.93	Dolostone/Schist
CMC 05-05	12.5	28.3	15.8	Dolostone
CMC 05-05	28.3	30.3	2	Sil/Oxid/Stwk
CMC 05-05	30.3	45.2	14.9	Dolostone
CMC 05-05	45.2	51.2	6	Granodiorite
CMC 05-06	0	1.5	1.5	Casing
CMC 05-06	1.5	4.9	3.4	Road Fill
CMC 05-06	4.9	23.05	18.15	Schist/Dolostone
CMC 05-06	23.05	34.1	11.05	Schist
CMC 05-06	34.1	38.1	4	Dacite?
CMC 05-07	0	3	3	Casing
CMC 05-07	3	17.7	14.7	Dolostone
CMC 05-07	17.7	20.7	3	SAND
CMC 05-07	20.7	36.25	15.55	Dolostone
CMC 05-07	36.25	43	6.75	LST
CMC 05-07	43	43.9	0.9	Gravel
CMC 05-07	43.9	45.1	1.2	LST
CMC 05-08	0	1.52	1.52	Casing
CMC 05-08	1.52	15.1	13.58	Dolostone
CMC 05-08	15.1	52.7	37.6	Schist?
CMC 05-08	21.1	52.7	31.6	Schist
CMC 05-09	0	6.1	6.1	Casing
CMC 05-09	6.1	6.5	0.4	Sluff
CMC 05-09	6.5	29.6	23.1	?+Schist
CMC 05-09	29.6	41.6	12	Granodiorite
CMC 05-09	41.6	47.9	6.3	Granodiorite
CMC 05-10	0	1.52	1.52	Casing
CMC 05-10	1.52	45.1	43.58	Granodiorite
CMC 05-11	0	1.52	1.52	Casing
CMC 05-11	1.52	27.85	26.33	Granodiorite
CMC 05-11	27.85	27.97	0.12	Granodiorite/Vein

CMC 05-11	27.97	39	11.03	Granodiorite
CMC 05-12	0	2.13	2.13	Casing
CMC 05-12	2.13	13.7	11.57	Granodiorite
CMC 05-12	13.7	16.2	2.5	Granodiorite/Vein
CMC 05-12	16.2	67.4	51.2	Granodiorite
CMC 05-13	0	1.23	1.23	Granodiorite
CMC 05-13	1.23	1.92	0.69	Granodiorite/Vein
CMC 05-13	1.92	10.1	8.18	Granodiorite
CMC 05-14	0	3.04	3.04	Casing
CMC 05-14	3.04	22	18.96	Granodiorite
CMC 05-14	22	23.65	1.65	Granodiorite/Vein
CMC 05-14	23.65	69.5	45.85	Granodiorite

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-01	1.52	2.51	0.99	P	cy	M	
CMC 05-01	4.8	5.7	0.9		qtz-chl-(biot?)	S	
CMC 05-01	8.29	8.58	0.29		qtz-chl-(biot?)+/-ser	M	
CMC 05-01	8.29	8.98	0.69	F	cy	W/M	
CMC 05-01	8.98	9.31	0.33		qtz-chl+/-ser	W/T	
CMC 05-01	10.09	10.69	0.6		qtz-chl	M	
CMC 05-01	11.08	11.09	0.01	Seam	cy		
CMC 05-01	11.48	11.64	0.16	F and P	MnO2	S	30
CMC 05-01	11.85	14.01	2.16		qtz-chl+/-biot?	M	
CMC 05-01	11.85	14.01	2.16	vnlt	qtz+/-hem+/-goe	W	
CMC 05-01	15.15	16.78	1.63		qtz-chl+/-ser	W	
CMC 05-01	17.6	18.26	0.66		qtz-chl+/-ser		
CMC 05-01	19.23	19.53	0.3		qtz-chl+/-biot?	M	
CMC 05-01	19.53	19.83	0.3	P	cy	M	
CMC 05-01	19.53	20.63	1.1		qtz-chl-biot?	M	
CMC 05-01	21.63	23.5	1.87		qtz-chl-biot?	W/M	
CMC 05-01	23.64	26.6	2.96	PS	cy	W	1
CMC 05-01	23.64	26.6	2.96	MS	ser	W	0.5
CMC 05-01	26.6	32.26	5.66	P	qtz	S	30
CMC 05-01	26.6	32.26	5.66	P	goe	S	10
CMC 05-01	26.6	30.83	4.23		chl	M	1
CMC 05-01	27.51	28.21	0.7	F	MnO2	S	15
CMC 05-01	27.51	28.21	0.7	P	qtz	S	
CMC 05-01	28.84	28.94	0.1	P	goe	S	
CMC 05-01	28.84	28.94	0.1	F	MnO2	S	
CMC 05-01	32.26	48.17	15.91		qtz-chl	S	
CMC 05-01	32.26	48.17	15.91	vnlt	qtz	W	
CMC 05-01	34.71	35.83	1.12	P	goe	S	
CMC 05-01	34.71	35.83	1.12	Patches	py	M	2
CMC 05-01	39.34	40.12	0.78	F	cy (kaol-smectite)	S	
CMC 05-01	41	41.4	0.4	P	goe	M	
CMC 05-01	41.92	42.23	0.31	P	qtz-chl	S	
CMC 05-01	45.12	45.17	0.05	P	qtz-chl	S	
CMC 05-01	47.8	48.17	0.37	P	qtz-chl	S	
CMC 05-01	48.17	52.9	4.73	P	qtz	W	
CMC 05-01	48.17	52.9	4.73	vnlt	qtz	W	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-01	48.17	52.9	4.73	stwk	qtz	T	
CMC 05-01	52.9	64.94	12.04	P	qtz-chl	M	
CMC 05-01	52.9	64.94	12.04	D	ser	T	
CMC 05-01	52.9	64.94	12.04	D	py	W	
CMC 05-01	52.9	64.94	12.04	PS	cy (kaol-smectite)	W	0.5
CMC 05-01	57.6	58.6	1	F	cy	W	
CMC 05-02	2.13	2.7	0.57	P	cy	S	
CMC 05-02	2.13	2.7	0.57	F	lim	M	
CMC 05-02	2.7	2.8	0.1	P	qtz	S	
CMC 05-02	2.8	7.1	4.3	F	lim	W	
CMC 05-02	2.8	3.5	0.7	P	cy	S	
CMC 05-02	3.5	7.1	3.6	P	cy	W	
CMC 05-02	7.1	7.6	0.5	P	qtz	S	
CMC 05-02	7.1	7.6	0.5	F	lim	M	
CMC 05-02	7.6	10.25	2.65	P	cy	M	
CMC 05-02	7.6	18	10.4	F	goe-lim	W	
CMC 05-02	10.25	10.5	0.25	P	qtz	S	
CMC 05-02	10.5	11	0.5	P	cy	W/M	
CMC 05-02	11	11.1	0.1	P	qtz	S	
CMC 05-02	11.1	11.75	0.65	P	cy	W	
CMC 05-02	11.75	13.2	1.45	P	qtz	S	
CMC 05-02	13.2	13.7	0.5	P	cy	M	
CMC 05-02	13.7	13.85	0.15	P	cy	S	
CMC 05-02	13.85	22.87	9.02	P	cy	M	
CMC 05-02	18	23	5	F	goe-lim-MnO ₂	W	
CMC 05-02	20	20.3	0.3	P	qtz	S	
CMC 05-02	20.65	21.6	0.95	P	qtz	S	
CMC 05-02	22.87	23.92	1.05	P	qtz	S	
CMC 05-02	23.92	26.6	2.68	P	cy	M/S	
CMC 05-02	23.92	26.6	2.68	P	qtz	M	
CMC 05-02	26.6	26.85	0.25	P	cy	M/S	
CMC 05-02	26.85	27.85	1	P	cy	M	
CMC 05-02	26.85	27.85	1	P	qtz	M	
CMC 05-02	27.85	28.8	0.95	P	cy	M/S	
CMC 05-02	27.85	28.8	0.95	P	qtz-chl	M	
CMC 05-02	28.8	29.2	0.4	P	cy	S	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-02	28.8	29.2	0.4		chl	T	
CMC 05-02	29.5	29.9	0.4	P	cy	S	
CMC 05-02	29.5	29.9	0.4		chl	T	
CMC 05-02	30.1	30.35	0.25	P	cy	S	
CMC 05-02	30.1	30.35	0.25		chl	T	
CMC 05-02	30.35	30.75	0.4	P	qtz	M/S	
CMC 05-02	31.5	32.35	0.85	P	cy	S	
CMC 05-02	31.5	32.35	0.85		chl	T	
CMC 05-02	32.6	33.35	0.75	P	cy	S	
CMC 05-02	32.6	33.35	0.75		chl	T	
CMC 05-02	33.35	33.8	0.45	P	qtz	S	
CMC 05-02	36	38.11	2.11	P	cy	W/M	
CMC 05-02	36	38.11	2.11	P	qtz	M	
CMC 05-02	38.11	38.61	0.5	P	cy	W/M	
CMC 05-02	38.11	38.61	0.5	P	qtz	M	
CMC 05-02	38.61	39.75	1.14	P	cy	W	
CMC 05-02	38.61	39.75	1.14	P	qtz	M	
CMC 05-02	39.75	40.4	0.65	P	cy	S	
CMC 05-02	39.75	40.4	0.65	F	lim	W	
CMC 05-02	40.4	42.1	1.7	P	cy	W/M	
CMC 05-02	40.4	42.1	1.7	P	qtz	M	
CMC 05-02	42.1	44	1.9	P	cy	M	
CMC 05-02	44	47.25	3.25	P	qtz	M/S	
CMC 05-02	44	47.25	3.25	P	cy	W/M	
CMC 05-02	47.25	47.5	0.25	P	cy	S	
CMC 05-02	47.25	47.5	0.25	F	lim	W	
CMC 05-02	47.5	48.5	1	P	qtz	M/S	
CMC 05-02	47.5	48.5	1	P	cy	W/M	
CMC 05-02	48.5	53.5	5	P	cy	W	
CMC 05-02	48.5	53.5	5	P	qtz+/-biot+/-py	M/S	
CMC 05-02	53.5	53.7	0.2	P	cy	M	
CMC 05-02	53.7	58.05	4.35	P	qtz	S	
CMC 05-02	53.7	58.05	4.35	P	cy	W/M	
CMC 05-02	58.05	58.25	0.2	P	cy	M/S	
CMC 05-02	58.25	59.45	1.2	P	qtz	S	
CMC 05-02	58.25	59.45	1.2	P	cy	W/M	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-03	3.05	9.1	6.05	PS+F	cy	M/S	
CMC 05-03	3.05	9.1	6.05	P	qtz	W/M	
CMC 05-03	9.1	13.7	4.6	P	qtz	M/S	
CMC 05-03	9.1	13.7	4.6	P	cy	W/M	
CMC 05-03	13.7	14.3	0.6	P	cy	M/S	
CMC 05-03	13.7	14.3	0.6	P	sil	M	
CMC 05-03	14.3	20.23	5.93	P	sil	M/S	
CMC 05-03	14.3	20.23	5.93	P	cy	W	
CMC 05-03	18	20.23	2.23	F	cy	M	
CMC 05-03	20.23	25.6	5.37	P	cy	M	
CMC 05-03	20.23	22.1	1.87	P	sil	M/S	
CMC 05-03	22.1	29	6.9	P	qtz	M	
CMC 05-03	25.6	29	3.4	P	cy	M/S	
CMC 05-03	29	39.7	10.7	P	qtz	M/S	
CMC 05-03	29	39.7	10.7	P	cy	W	
CMC 05-03	29	39.7	10.7	F	cy	M	
CMC 05-03	39.7	47.9	8.2	P	qtz	W/M	
CMC 05-03	39.7	47.9	8.2	PS	cy	W/M	
CMC 05-03	47.9	49.1	1.2	P	qtz	S	
CMC 05-03	47.9	49.1	1.2	F	cy	W	
CMC 05-04	3.05	5.15	2.1	P	cy	M	
CMC 05-04	3.05	5.15	2.1	F	cy	M/S	
CMC 05-04	3.05	5.15	2.1	F	chl/ser	W/M	
CMC 05-04	5.15	10.3	5.15	P	qtz	M/S	
CMC 05-04	5.15	10.3	5.15	F	cy	W	
CMC 05-04	10.3	17.1	6.8	P	qtz	M/S	
CMC 05-04	10.3	12	1.7	P	cy	W/M	
CMC 05-04	12	17.1	5.1	P	cy	M/S	
CMC 05-04	17.1	25.2	8.1	P	qtz	M/S	
CMC 05-04	17.1	25.2	8.1	P	cy	M	
CMC 05-04	17.1	25.2	8.1	F	cy	M/S	
CMC 05-04	25.2	33.5	8.3	P	qtz	M/S	
CMC 05-04	25.2	33.5	8.3	F	cy	W	
CMC 05-04	28.8	29.35	0.55	P	cy	S	
CMC 05-04	28.8	29.35	0.55	P	MnO2	S	
CMC 05-04	29.9	30.4	0.5	P	cy	S	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-04	29.9	30.4	0.5	P	MnO2	S	
CMC 05-04	33.5	35	1.5	P	qtz	M/S	
CMC 05-04	33.5	35	1.5	F	cy	W	
CMC 05-04	35	36.9	1.9	P	sil	S	
CMC 05-04	35	36.9	1.9	D	ep	S	
CMC 05-04	36.9	48.3	11.4	P	qtz	S	
CMC 05-04	36.9	48.3	11.4	F	cy	W	
CMC 05-04	43.3	43.7	0.4	P	cy	S	
CMC 05-04	43.3	43.7	0.4	P	MnO2	S	
CMC 05-04	48.3	56.25	7.95	P	sil	M	
CMC 05-04	48.3	56.25	7.95	P	cy	M/S	
CMC 05-04	48.3	56.25	7.95	F	cy	S	
CMC 05-04	56.25	60.2	3.95	P	sil	M	
CMC 05-04	56.25	60.2	3.95	P	cy	M	
CMC 05-04	56.25	60.2	3.95	F	cy	M/S	
CMC 05-04	60.2	62.6	2.4	P	sil	M/S	
CMC 05-04	60.2	62.6	2.4	P	ep	M	
CMC 05-04	60.2	62.6	2.4	F	cy	W/M	
CMC 05-05	4.57	12.5	7.93	P	sil	W	
CMC 05-05	4.57	12.5	7.93	F	cy	W/M	
CMC 05-05	12.5	28.3	15.8	P	sil	M	
CMC 05-05	12.5	28.3	15.8	P	cy	S	
CMC 05-05	21.15	21.35	0.2		MnO2/Goe/Qtz		
CMC 05-05	28.3	30.3	2	P	sil	M/S	
CMC 05-05	28.3	30.3	2	P	MnO2/Goe	S	
CMC 05-05	28.3	30.3	2	V	MnO2/Goe	S	
CMC 05-05	28.3	30.3	2	F	cy	W/M	
CMC 05-05	28.3	30.3	2	Vug	MnO2/Goe		
CMC 05-05	30.3	40.5	10.2	P	Sil	M/S	
CMC 05-05	30.3	40.5	10.2	P	cy	M	
CMC 05-05	30.3	40.5	10.2	F	cy	M/S	
CMC 05-05	40.5	43.6	3.1	P	sil	M	
CMC 05-05	40.5	43.6	3.1	P	cy	M/S	
CMC 05-05	43.6	45.2	1.6	P	sil	M	
CMC 05-05	43.6	45.2	1.6	P	cy	M	
CMC 05-05	43.6	45.2	1.6	V	MnO2/Goe	S	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-05	45.2	50	4.8	P	sil	M	
CMC 05-05	45.2	50	4.8	P	Cy	W/M	
CMC 05-05	45.2	50	4.8	F	Cy	M	
CMC 05-05	45.2	50	4.8	P	Ep	W	
CMC 05-05	50	51.2	1.2	P	Sil	M	
CMC 05-05	50	51.2	1.2	P	Cy	M	
CMC 05-05	50	51.2	1.2	F	Cy	W	
CMC 05-05	50	51.2	1.2	P	Ep	W/M	
CMC 05-06	4.9	23.05	18.15	P	Qtz/chl/ser	W	
CMC 05-06	4.9	10.35	5.45	Vnlt	MnO2	W	
CMC 05-06	7.95	8.3	0.35	F	MnO2	W	
CMC 05-06	8.5	8.85	0.35	F	cy	M	
CMC 05-06	17	18.3	1.3	Sk	qtz-chl-ep+/-gnt	M	
CMC 05-06	17.4	17.8	0.4	P	cy+MnO2	S	
CMC 05-06	18.7	19.4	0.7	P	cy+MnO2	S	
CMC 05-06	19.6	20.3	0.7	Sk	qtz-chl-gnt-Ep	T	
CMC 05-06	23.8	24.45	0.65	gg	cy	S	
CMC 05-06	26.3	29.85	3.55	P	MnO2	S	
CMC 05-06	26.3	27	0.7	P	cy	T/W	
CMC 05-06	28.85	29.85	1	V	MnO2	M	
CMC 05-06	28.85	29.85	1	Vug	Qtz	M	
CMC 05-06	29.85	34.1	4.25	P	MnO2	M	
CMC 05-06	29.85	33.05	3.2	P	cy	T	
CMC 05-06	33.05	34.1	1.05	P	cy	W	
CMC 05-06	34.1	35.6	1.5	P	MnO2	M	
CMC 05-06	35.6	36.2	0.6	P	MnO2	S	
CMC 05-06	36.2	37.2	1	Mot	cy	S	
CMC 05-06	37.2	38.1	0.9	Mot	Goe/Hem	S	
CMC 05-07	3.1	6.85	3.75	Mot	cy	W	
CMC 05-07	3.1	6.85	3.75	Mot	MnO2/Goe	W	
CMC 05-07	3.1	6.85	3.75	Sk	Gnt-chl-qtz	S	
CMC 05-07	3.45	5.15	1.7	P	MnO2	S	40
CMC 05-07	3.45	5.15	1.7	Vug	Vug	T	
CMC 05-07	3.45	5.15	1.7	M	Goe	M	10
CMC 05-07	6.25	6.45	0.2	P	cy		
CMC 05-07	6.85	8.4	1.55	P	MnO2+Qtz	W	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-07	6.85	8.4	1.55	P	Goe	S	
CMC 05-07	8.4	10.6	2.2	P	MnO2	S	
CMC 05-07	8.4	10.6	2.2	V/F	qtz	M	10
CMC 05-07	8.4	10.6	2.2	M	goe	M	10
CMC 05-07	6.85	11	4.15	P	Qtz	M	
CMC 05-07	10.6	11	0.4	Mot	Goe	W	
CMC 05-07	11	17.7	6.7	P	Goe	S	
CMC 05-07	11	17.7	6.7	Vug	Vug	M	
CMC 05-07	11.85	14.75	2.9	P	Goe	S	25
CMC 05-07	11.85	14.75	2.9	Mot/Stwk	MnO2	M	10
CMC 05-07	12.05	13	0.95	Vug	Vug	S	
CMC 05-07	14.75	17.6	2.85	P	MnO2	S	25
CMC 05-07	14.75	17.6	2.85	Mot	cy	M	5
CMC 05-07	17.6	17.7	0.1	F	cy	M	
CMC 05-07	20.7	23.15	2.45	P	sil	S	
CMC 05-07	20.7	23.15	2.45	Vug	sil	M	
CMC 05-07	20.7	23.15	2.45	P	goe	S	
CMC 05-07	20.7	23.15	2.45	F	MnO2	W	
CMC 05-07	23.15	23.7	0.55	P	MnO2	S	50
CMC 05-07	23.15	23.7	0.55	P	Goe	M	10
CMC 05-07	23.7	25.9	2.2	gg	cy	M	
CMC 05-07	23.7	25.9	2.2	P	MnO2	S	
CMC 05-07	25.9	28.7	2.8	P	Goe	W	2
CMC 05-07	25.9	28.7	2.8	Frac/Vnlt	MnO2	W	1
CMC 05-07	31.55	32.95	1.4	P	cy	W	1
CMC 05-07	31.55	32.95	1.4	Vnlt/Stwk	MnO2	S	
CMC 05-07	31.55	32.95	1.4	P	Goe	M	10
CMC 05-07	31.55	32.95	1.4	M	cy	T	0.1
CMC 05-07	32.95	36.25	3.3	P	Sil	W	
CMC 05-07	32.95	36.25	3.3	F	Goe	M	7
CMC 05-07	32.95	36.25	3.3	P	Goe	M	7
CMC 05-07	32.95	36.25	3.3	Vnlt	MnO2	T	0.5
CMC 05-07	33.85	34.35	0.5	P	MnO2	S	
CMC 05-07	36.25	43	6.75	Sk	Gnt-chl-qtz-ep	S	
CMC 05-07	36.25	43	6.75	vnlt	cal	S	20
CMC 05-07	37.6	38.3	0.7	vnlt	chl	M	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-07	43	43.9	0.9	P	MnO2	T	
CMC 05-07	43	43.9	0.9	P	Goe	T	
CMC 05-07	43.9	45.1	1.2	Sk	Gnt-chl-qtz-ep	S	
CMC 05-08	1.52	15.1	13.58	Sk	Gnt-qtz-chl-ep	S	
CMC 05-08	1.52	15.1	13.58	F	goe	T	
CMC 05-08	1.52	15.1	13.58	F	MnO2	T	
CMC 05-08	1.52	15.1	13.58	Vnlt/Interstitial	cal	S	5
CMC 05-08	12.25	12.75	0.5	Replace?	ep over gnt?	W	
CMC 05-08	13.05	13.1	0.05	F	cy	S	
CMC 05-08	14	14.3	0.3	Replace?	ep over gnt?	W	
CMC 05-08	14.7	14.8	0.1	V	gnt	S	
CMC 05-08	15.1	21.1	6	P	Qtz-chl-ser	S	
CMC 05-08	19.8	21.1	1.3	P	Goe	S	
CMC 05-08	20.7	21	0.3	Sk	qtz-gnt	W	
CMC 05-08	21.1	23	1.9	P	Goe	S	
CMC 05-08	21.1	23	1.9	M	MnO2	S	
CMC 05-08	23	23.25	0.25	P	MnO2	S	
CMC 05-08	23	23.25	0.25	V	Qtz		
CMC 05-08	23.25	24	0.75	Vug	Vug	S	10
CMC 05-08	23.25	24	0.75	Vug	Qtz	M	5
CMC 05-08	23.25	24	0.75	P	MnO2	S	80
CMC 05-08	24	24.6	0.6	P	Goe	S	
CMC 05-08	24	24.6	0.6	F	MnO2	M	
CMC 05-08	24	24.6	0.6	gg	Cy	W	
CMC 05-08	24.6	25	0.4	P	Goe/Hem	S	50
CMC 05-08	24.6	25	0.4	P	MnO2	S	50
CMC 05-08	24.6	25	0.4	M	cy	T	
CMC 05-08	25.1	25.45	0.35	P	MnO2	80	
CMC 05-08	25.45	25.65	0.2	P	Goe	W	
CMC 05-08	25.45	25.65	0.2	F	cy	M	
CMC 05-08	25.45	25.65	0.2	vnlt	sil/MnO2	W	
CMC 05-08	26.5	29.15	2.65	P	Qtz	S	45
CMC 05-08	26.5	29.15	2.65	P	MnO2	S	30
CMC 05-08	26.5	29.15	2.65	M	Goe/Hem	S	25
CMC 05-08	29.15	30.8	1.65	P	MnO2	S	80
CMC 05-08	29.15	30.8	1.65	M	Goe	S	20

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-08	29.15	29.3	0.15	gg	cy+goe	S	80
CMC 05-08	29.5	29.6	0.1	gg	cy+goe	S	
CMC 05-08	29.9	30.1	0.2	gg	cy+goe	S	
CMC 05-08	30.4	30.8	0.4	gg	cy+goe	S	
CMC 05-08	30.8	31	0.2	M	MnO2	M	10
CMC 05-08	30.8	31	0.2	P	Goe	W	3
CMC 05-08	31	34.7	3.7	P	Goe	M	5
CMC 05-08	31	34.7	3.7	Foln	MnO2	W	1
CMC 05-08	34.7	36	1.3	Stwk	qtz-MnO2-Goe	W	
CMC 05-08	36	36.2	0.2	gg	cy	S	
CMC 05-08	36.2	40.5	4.3	P	Goe	M	8
CMC 05-08	36.2	40.5	4.3	F	MnO2	W	
CMC 05-08	40.5	52.7	12.2	P	qtz-chl-carb	S	
CMC 05-08	40.5	41.4	0.9	sk	cal-ep-chl-gnt	S	
CMC 05-08	41.4	52.7	11.3	P	qtz-chl-ser	S	
CMC 05-08	41.4	52.7	11.3	sk	qtz-gnt-ep	T	
CMC 05-08	43.7	45.85	2.15	M	qtz-Fe Carb	M	
CMC 05-08	45.85	52.7	6.85	M	qtz-Fe Carb	W	
CMC 05-09	6.5	19.6	13.1	stwk	MnO2	S	60
CMC 05-09	6.5	19.6	13.1	M	hem	S	15
CMC 05-09	6.5	19.6	13.1	M	goe	M	10
CMC 05-09	6.5	19.6	13.1	D	qtz	W	
CMC 05-09	9.25	9.5	0.25	Vug	qtz	W	
CMC 05-09	10.6	11.9	1.3	Vug	qtz	S	10
CMC 05-09	18.3	19.6	1.3	P	Goe	S	50
CMC 05-09	18.3	19.6	1.3	Band	MnO2	M	
CMC 05-09	19.6	20.3	0.7	Stwk	MnO2	S	
CMC 05-09	19.6	20.3	0.7	P	cy	W	2
CMC 05-09	20.3	21.65	1.35	V	qtz	S	
CMC 05-09	20.3	21.65	1.35	Stwk	MnO2	M	
CMC 05-09	20.3	21.65	1.35	Vnlt	Goe	W	
CMC 05-09	21.65	22.3	0.65	M	cy	W	2
CMC 05-09	21.65	22.3	0.65	P	MnO2	W	3
CMC 05-09	21.65	22.3	0.65	M	Goe	M	5
CMC 05-09	22.3	23.95	1.65	P	MnO2+Sil	S	30
CMC 05-09	23.95	28.7	4.75	P	MnO2	S	30

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-09	23.95	28.7	4.75	P	Goe	S	30
CMC 05-09	23.95	28.7	4.75	Vug	qtz	S	25
CMC 05-09	23.95	28.7	4.75	M	cy	S	10
CMC 05-09	23.95	28.7	4.75	stwk	qtz	S	5
CMC 05-09	28.7	29.9	1.2	F+Bx	goe	M	
CMC 05-09	28.7	29.9	1.2	M	cy	T	
CMC 05-09	29.9	41.6	11.7	P	goe	S	15
CMC 05-09	29.9	41.6	11.7	vnlt/stwk	MnO2	M	
CMC 05-09	33.25	34.2	0.95	F	cy	S	
CMC 05-09	34.5	34.52	0.02	V	Goe-MnO2-ser	S	
CMC 05-09	36.1	36.25	0.15	P	cy	W	1
CMC 05-09	36.1	36.25	0.15	M	MnO2-Goe	W	3
CMC 05-09	37.25	38.2	0.95	P	qtz	M	2
CMC 05-09	37.25	38.2	0.95	vnlt	MnO2	W	
CMC 05-09	38.9	39.3	0.4	P	qtz-ser-chl	S	
CMC 05-09	38.9	39.3	0.4	vnlt	qtz	W	
CMC 05-09	39.3	41.6	2.3	F+Vnlt	MnO2-Goe	M	5
CMC 05-09	39.3	41.6	2.3	P	cy	T	
CMC 05-09	41.6	47.9	6.3	P	qtz-chl-ser	M	
CMC 05-10	2	2.35	0.35	P	qtz	T	0.5
CMC 05-10	2.75	3.8	1.05	F	cy	W	2
CMC 05-10	2.75	3.8	1.05	P	goe	W	
CMC 05-10	2.75	4.5	1.75	PS	cy	W	
CMC 05-10	3.75	5.1	1.35	F	goe	W	1
CMC 05-10	3.75	5.1	1.35	F	MnO2	W	
CMC 05-10	4.5	10.6	6.1	P	qtz-chl-ser	M	
CMC 05-10	4.5	10.6	6.1	M+PS	cy	W	
CMC 05-10	7.8	8.2	0.4	P	goe	M	
CMC 05-10	7.8	8.05	0.25	P+PS	cy	W	
CMC 05-10	8.05	8.2	0.15	F	cy	W	
CMC 05-10	8.2	9.5	1.3	PS	goe	T	0.5
CMC 05-10	8.2	9.5	1.3	F	cy	W	
CMC 05-10	10.6	11.05	0.45	P	qtz-chl	W	
CMC 05-10	11.05	11.2	0.15	PS	cy	M	10
CMC 05-10	11.05	11.2	0.15	P	MnO2	W	
CMC 05-10	11.3	14.3	3	PS	cy	T	0.5

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-10	11.3	14.3	3	P	sil	T	0.5
CMC 05-10	11.3	14.3	3	P	goe	S	
CMC 05-10	14.3	14.45	0.15	P	cy	W	
CMC 05-10	15	15.2	0.2	F	cy	S	
CMC 05-10	15.2	23	7.8	P	qtz-chl-ser	M	
CMC 05-10	15.2	23	7.8	D	ser	T	
CMC 05-10	15.2	23	7.8	PS	cy	T	
CMC 05-10	21.1	21.5	0.4	P	cy+goe	S	
CMC 05-10	23	43.9	20.9	D	ser	T	0.5
CMC 05-10	23	43.9	20.9	P	goe	W	1
CMC 05-10	23	43.9	20.9	PS	cy	T	0.5
CMC 05-10	35.77	35.97	0.2	P	qtz-ser-chl	W	
CMC 05-10	36.3	36.95	0.65	P	qtz-chl-ser	T	
CMC 05-10	37.3	37.75	0.45	F	cy	W	2
CMC 05-10	37.3	37.75	0.45	P	goe	M	5
CMC 05-10	37.8	38.7	0.9	P	qtz-ser	W	2
CMC 05-10	43.9	45.1	1.2	F	cy	S	
CMC 05-10	43.9	45.1	1.2	Mot	cy	T	
CMC 05-11	1.52	9.55	8.03	P	goe	W	2
CMC 05-11	1.52	9.55	8.03	F	MnO2	W	1
CMC 05-11	1.52	21.5	19.98	D	ser	T	0.3
CMC 05-11	5.1	5.3	0.2	stwk	MnO2	S	
CMC 05-11	5.3	5.85	0.55	P	MnO2	S	60
CMC 05-11	5.3	5.85	0.55	Mot	goe	M	10
CMC 05-11	5.85	6.05	0.2	stwk	MnO2	S	
CMC 05-11	6.8	8.7	1.9	P	qtz-ser-chl	M	2
CMC 05-11	6.8	8.7	1.9	ser	ser	W	1
CMC 05-11	6.8	8.7	1.9	vnlt	goe	W	
CMC 05-11	9.55	11.3	1.75	Mot	goe	T	
CMC 05-11	9.55	11.3	1.75	P	qtz	W	1
CMC 05-11	9.55	11.3	1.75	PS	cy	T	0.5
CMC 05-11	9.7	9.9	0.2	P	qtz-chl	W	0.5
CMC 05-11	11	11.9	0.9	P	goe	W	1
CMC 05-11	12	13.05	1.05	vnlt/Mot	MnO2/vnlts	W	0.75
CMC 05-11	15.5	15.9	0.4	F	goe	M	
CMC 05-11	15.9	16.8	0.9	PS	ep-ser	M	

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-11	17.3	21.5	4.2	P	goe	M	5
CMC 05-11	20.7	21.5	0.8	P	qtz	W	1
CMC 05-11	21.5	39	17.5	F	goe	T	0.5
CMC 05-11	21.5	22.3	0.8	P	cy	S	100
CMC 05-11	22.3	22.95	0.65	P	qtz	S	40
CMC 05-11	22.3	22.95	0.65	D	ser	W	2
CMC 05-11	22.95	24.05	1.1		ser	W	
CMC 05-11	22.95	24.05	1.1	V	qtz	T	0.5
CMC 05-11	24.8	26.7	1.9	V	qtz-ser	T	0.1
CMC 05-11	26.5	26.65	0.15	PS	cy	M	
CMC 05-11	28.4	29.55	1.15	PS	cy	T	0.75
CMC 05-11	29.55	39	9.45	Mot	qtz-chl-ser	M	
CMC 05-11	29.55	39	9.45	vnlt	qtz		
CMC 05-11	29.55	39	9.45	D	ser	W	1
CMC 05-11	29.55	39	9.45	V	qtz	W	1
CMC 05-11	29.55	39	9.45	F	goe	T	0.5
CMC 05-13	0	1.23	1.23	stwk	MnO2	M	5
CMC 05-13	0.9	1.23	0.33	P	cy	S	
CMC 05-13	1.23	1.92	0.69	P	goe	M	3
CMC 05-13	1.23	1.92	0.69	F	MnO2	T	0.1
CMC 05-13	1.23	1.92	0.69	P	qtz	T	
CMC 05-13	1.92	8.52	6.6	PS	cy	W	0.5
CMC 05-13	2.5	2.65	0.15	F	cy	W	1
CMC 05-13	2.8	2.85	0.05	F	MnO2	W	
CMC 05-13	4	4.3	0.3	D	ser	W	1
CMC 05-13	4.6	4.8	0.2	F	cy	W	1
CMC 05-13	4.8	5.1	0.3	F	cy	W	0.5
CMC 05-13	4.8	5.1	0.3	D	ser	W	0.5
CMC 05-13	8.52	8.8	0.28	P	cy	S	8
CMC 05-13	8.52	8.8	0.28	D	ser	W	
CMC 05-13	8.52	8.8	0.28	P	goe	W	
CMC 05-13	9	10.1	1.1	PS	cy	S	5
CMC 05-14	3.45	5.4	1.95	P	qtz-chl-ser	S	5
CMC 05-14	3.45	5.4	1.95	vnlt	qtz	W	
CMC 05-14	3.45	5.4	1.95	Mot	goe	W	
CMC 05-14	5.4	8.35	2.95	P	qtz-chl	W	1

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-14	6.4	6.7	0.3	F	cy	S	
CMC 05-14	6.4	6.7	0.3	vnlt	goe	W	
CMC 05-14	8.35	11.85	3.5	PS	cy	M	2
CMC 05-14	8.35	11.85	3.5	P	goe	W	1
CMC 05-14	10.55	10.85	0.3	P	qtz-chl	S	
CMC 05-14	11.85	13.7	1.85	P	qtz-chl-ser	S	7
CMC 05-14	11.85	13.7	1.85	vnlt	qtz	W	
CMC 05-14	11.85	13.7	1.85	vnlt	goe	W	
CMC 05-14	13.7	20	6.3	F	goe	S	
CMC 05-14	13.9	14.2	0.3	D	ser	W	0.5
CMC 05-14	14.2	14.35	0.15	F	goe-qtz-ser-hem	W	
CMC 05-14	14.56	14.68	0.12	PS	cy	W	
CMC 05-14	15.7	18.3	2.6	D	ser	S	10
CMC 05-14	17.5	17.7	0.2	P	goe	M	
CMC 05-14	18.3	18.7	0.4	D	ser	W	0.5
CMC 05-14	18.7	19.33	0.63	P	qtz-chl-ser	S	5
CMC 05-14	19.33	20	0.67	F	goe-MnO2	W	
CMC 05-14	20	22	2	P	cy	W	
CMC 05-14	22	23.65	1.65	P	qtz	M	
CMC 05-14	22	23.65	1.65	V	qtz	M	
CMC 05-14	23.65	23.95	0.3	P	cy	S	10
CMC 05-14	23.95	24.95	1	P	cy	W	1
CMC 05-14	25	25.1	0.1	P	qtz-chl	M	2
CMC 05-14	25.1	28.45	3.35	P	qtz	W	0.5
CMC 05-14	25.1	28.45	3.35	PS	cy	T	0.1
CMC 05-14	28.45	29	0.55	P	qtz-chl-ser	S	5
CMC 05-14	29.5	30.3	0.8	D	ser	W	1
CMC 05-14	30.3	38.1	7.8	P	qtz	T	
CMC 05-14	31.44	33.45	2.01	F	cy-goe	T	0.2
CMC 05-14	32.9	33.45	0.55	F	cy	W	2
CMC 05-14	36.5	40.12	3.62	F	goe	W	1
CMC 05-14	38.1	43.2	5.1	P	qtz-chl	S	10
CMC 05-14	38.1	43.2	5.1	PS	cy	T	0.2
CMC 05-14	41.65	42.3	0.65	PS	cy	M	2
CMC 05-14	43.2	43.8	0.6	P	cy	S	8
CMC 05-14	43.2	47.2	4	PS	cy	T	0.1

ALTERATION LOG

Drill Hole	From (m)	To (m)	Interval (m)	Occurrence	Alteration	Strength	% age
CMC 05-14	47.2	49.7	2.5	F	goe	W	0.5
CMC 05-14	47.2	49.7	2.5	P	cy	S	15
CMC 05-14	47.2	56.65	9.45	D	ser	T	0.2
CMC 05-14	47.7	50.4	2.7	P	cy	M	4
CMC 05-14	50.15	50.55	0.4	P	cy	S	
CMC 05-14	50.4	51.55	1.15	P	cy	S	18
CMC 05-14	51.55	56.65	5.1	P	qtz	T	0.1
CMC 05-14	51.55	56.65	5.1	PS	cy	T	0.1
CMC 05-14	56.65	61.45	4.8	P	cy	S	80
CMC 05-14	56.65	61.45	4.8	D	ser	W	0.5
CMC 05-14	61.45	67.5	6.05	P	qtz-chl	M	
CMC 05-14	61.45	67.5	6.05	P	cy	M	
CMC 05-14	61.45	67.5	6.05	PS	cy	W	
CMC 05-14	67.5	69.5	2	P	qtz-chl-ser	M	5

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-01	25501	10.75	11.50	0.75	0.002	0.003	<.01	0.06	<2	0.001	<.001	0.07	0.68	<.01	0.001	<.001	0.001
CMC 05-01	25502	11.50	11.65	0.15	0.016	0.008	0.13	0.62	7	0.001	0.001	1.44	6.08	0.01	0.008	0.002	0.002
CMC 05-01	25503	11.65	12.33	0.68	0.001	0.002	<.01	0.07	<2	<.001	<.001	0.06	0.89	<.01	0.001	<.001	<.001
CMC 05-01	25504	12.33	12.43	0.10	0.005	0.003	0.02	0.22	<2	0.001	<.001	1.25	5.16	<.01	0.007	0.001	0.001
CMC 05-01	25505	12.43	14.00	1.57	0.001	0.001	<.01	0.07	<2	<.001	<.001	0.09	1.3	<.01	0.003	<.001	0.001
CMC 05-01	25506	14.00	15.50	1.50	0.001	0.002	<.01	0.09	<2	<.001	<.001	0.08	1.58	<.01	0.002	<.001	<.001
CMC 05-01	25507	15.50	17.00	1.50	<.001	0.001	<.01	0.1	<2	<.001	<.001	0.06	1.46	<.01	0.002	<.001	0.001
CMC 05-01	25508	17.00	18.50	1.50	0.002	0.001	<.01	0.09	<2	<.001	<.001	0.08	1.82	<.01	0.003	<.001	<.001
CMC 05-01	25509	18.50	20.00	1.50	<.001	0.002	<.01	0.19	<2	<.001	<.001	0.04	1.62	<.01	0.001	<.001	<.001
CMC 05-01	25510	20.00	21.50	1.50	<.001	0.004	<.01	0.25	<2	0.001	0.001	0.04	1.5	<.01	0.001	0.001	<.001
CMC 05-01	25511	21.50	23.00	1.50	0.005	0.001	<.01	0.2	<2	<.001	<.001	0.03	1.34	<.01	0.001	<.001	0.001
CMC 05-01	25512	23.00	23.64	0.64	0.001	0.004	0.01	0.08	8	0.001	<.001	0.02	1.31	<.01	0.001	<.001	<.001
CMC 05-01	25513	23.64	26.60	2.96	0.002	0.002	0.11	0.31	6	0.001	<.001	0.58	2.06	<.01	0.002	0.001	0.002
CMC 05-01	25514	26.60	27.43	0.83	<.001	0.008	0.26	0.62	39	0.001	<.001	1.25	3.9	<.01	0.001	0.002	0.003
CMC 05-01	25515	27.43	28.19	0.76	0.001	0.008	0.05	1.24	15	0.001	<.001	1.69	5.91	<.01	0.002	0.003	<.001
CMC 05-01	25516	28.19	30.13	1.94	<.001	<.001	0.14	0.16	<2	<.001	<.001	0.43	1.94	<.01	0.003	<.001	<.001
CMC 05-01	25517	30.13	30.21	0.08	<.001	0.535	53.14	0.12	5886	<.001	<.001	0.29	3.35	0.02	<.001	0.002	0.666
CMC 05-01	25518	N/A	N/A	N/A	<.001	<.001	0.03	<.01	<2	0.001	<.001	0.01	0.11	<.01	0.004	<.001	<.001
CMC 05-01	25519	30.21	30.86	0.65	0.002	0.003	0.28	0.22	20	0.001	<.001	1.42	3.77	<.01	0.001	0.001	0.001
CMC 05-01	25566	30.86	31.60	0.74	0.001	0.001	0.01	0.11	3	<.001	<.001	0.05	1.97	<.01	0.001	<.001	<.001
CMC 05-01	25520	31.60	33.10	1.50	<.001	<.001	<.01	0.06	<2	<.001	<.001	0.05	1.52	<.01	0.002	<.001	<.001
CMC 05-01	25521	33.10	34.60	1.50	<.001	0.001	0.01	0.05	<2	0.001	<.001	0.1	1.51	<.01	0.002	<.001	0.001
CMC 05-01	25522	34.60	36.10	1.50	<.001	0.001	0.02	0.15	<2	<.001	<.001	0.06	3.17	0.01	0.001	0.001	0.001
CMC 05-01	25523	36.10	37.60	1.50	<.001	<.001	<.01	<.01	<2	0.001	<.001	0.04	1.58	<.01	0.005	<.001	<.001
CMC 05-01	25524	36.10	37.60	1.50	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.04	1.6	<.01	0.005	<.001	<.001
CMC 05-01	25525	37.60	39.10	1.50	<.001	<.001	<.01	<.01	<2	0.001	0.001	0.06	1.53	<.01	0.006	<.001	<.001
CMC 05-01	25526	39.10	40.60	1.50	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.05	1.56	<.01	0.006	<.001	0.001
CMC 05-01	25527	40.60	42.10	1.50	0.001	<.001	<.01	0.21	<2	<.001	0.001	0.09	1.53	<.01	0.003	0.001	<.001
CMC 05-01	25528	42.10	43.60	1.50	0.001	0.001	0.05	0.36	<2	<.001	<.001	0.21	1.68	<.01	0.002	0.001	0.001
CMC 05-01	25529	43.60	45.10	1.50	<.001	0.001	0.12	0.46	<2	0.001	<.001	0.89	2.85	<.01	0.001	0.002	0.002
CMC 05-01	25530	45.10	46.60	1.50	<.001	0.001	<.01	0.33	<2	0.001	<.001	0.06	1.87	<.01	0.003	0.001	0.001
CMC 05-01	25531	46.60	48.10	1.50	<.001	<.001	<.01	0.13	<2	0.001	<.001	0.07	1.5	<.01	0.01	<.001	0.001
CMC 05-01	25532	48.10	49.60	1.50	<.001	<.001	<.01	0.02	<2	<.001	<.001	0.05	1.54	<.01	0.011	<.001	<.001
CMC 05-01	25533	49.60	51.10	1.50	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.04	1.57	<.01	0.007	<.001	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-01	25501	10.75	11.50	0.75	<.01	0.09	0.021	0.001	0.03	0.53	0.01	0.26	<.001	0.001	<.01	2.8
CMC 05-01	25502	11.50	11.65	0.15	<.01	0.11	0.023	<.001	0.02	0.5	0.01	0.39	<.001	0.001	0.01	0.54
CMC 05-01	25503	11.65	12.33	0.68	<.01	0.11	0.028	0.001	0.07	0.62	<.01	0.28	<.001	<.001	<.01	2.81
CMC 05-01	25504	12.33	12.43	0.10	<.01	0.14	0.042	<.001	0.02	0.55	0.04	0.45	<.001	<.001	<.01	0.58
CMC 05-01	25505	12.43	14.00	1.57	<.01	0.74	0.071	0.001	0.05	0.64	0.01	0.32	<.001	0.001	0.01	6.53
CMC 05-01	25506	14.00	15.50	1.50	<.01	0.21	0.064	0.001	0.13	1	0.03	0.33	<.001	<.001	0.01	5.07
CMC 05-01	25507	15.50	17.00	1.50	<.01	0.32	0.063	<.001	0.12	0.86	0.06	0.3	<.001	<.001	0.01	5.34
CMC 05-01	25508	17.00	18.50	1.50	<.01	0.64	0.064	0.001	0.08	0.84	<.01	0.35	<.001	<.001	<.01	5.97
CMC 05-01	25509	18.50	20.00	1.50	<.01	0.21	0.057	0.001	0.14	0.91	0.07	0.36	<.001	<.001	<.01	5.9
CMC 05-01	25510	20.00	21.50	1.50	<.01	0.15	0.046	0.001	0.12	0.94	0.06	0.31	0.001	<.001	<.01	6.1
CMC 05-01	25511	21.50	23.00	1.50	<.01	0.13	0.033	<.001	0.08	0.85	0.03	0.29	<.001	<.001	<.01	5.25
CMC 05-01	25512	23.00	23.64	0.64	<.01	0.07	0.03	0.001	0.02	0.5	0.01	0.38	<.001	<.001	0.01	2.4
CMC 05-01	25513	23.64	26.60	2.96	<.01	0.06	0.036	0.001	0.01	0.49	<.01	0.45	<.001	<.001	<.01	4.29
CMC 05-01	25514	26.60	27.43	0.83	<.01	0.11	0.037	<.001	0.06	0.39	<.01	0.4	<.001	<.001	0.01	2.98
CMC 05-01	25515	27.43	28.19	0.76	<.01	0.11	0.046	<.001	0.08	0.48	0.04	0.47	<.001	<.001	0.02	3.15
CMC 05-01	25516	28.19	30.13	1.94	<.01	0.67	0.056	0.001	0.15	0.7	0.09	0.43	<.001	<.001	<.01	3.57
CMC 05-01	25517	30.13	30.21	0.08	<.01	<.01	0.005	<.001	0.01	0.19	<.01	0.15	<.001	<.001	0.53	0.85
CMC 05-01	25518	N/A	N/A	N/A	<.01	22.79	<.001	<.001	12.94	0.03	0.03	0.02	<.001	<.001	<.01	2.96
CMC 05-01	25519	30.21	30.86	0.65	<.01	0.22	0.052	<.001	0.13	0.47	<.01	0.47	<.001	<.001	<.01	2.72
CMC 05-01	25566	30.86	31.60	0.74	<.01	0.2	0.055	<.001	0.13	0.95	0.01	0.3	<.001	<.001	<.01	2.62
CMC 05-01	25520	31.60	33.10	1.50	<.01	0.68	0.058	0.001	0.28	0.86	0.04	0.34	<.001	<.001	<.01	6.06
CMC 05-01	25521	33.10	34.60	1.50	<.01	0.56	0.062	<.001	0.12	0.67	0.04	0.33	<.001	<.001	0.01	5.16
CMC 05-01	25522	34.60	36.10	1.50	<.01	0.29	0.058	<.001	0.1	0.71	0.04	0.36	<.001	<.001	<.01	5.74
CMC 05-01	25523	36.10	37.60	1.50	<.01	0.85	0.061	0.001	0.28	0.79	0.04	0.36	<.001	<.001	<.01	6.04
CMC 05-01	25524	36.10	37.60	1.50	<.01	0.94	0.062	0.001	0.29	0.79	0.06	0.32	<.001	<.001	<.01	5.45
CMC 05-01	25525	37.60	39.10	1.50	<.01	1.1	0.062	<.001	0.27	0.76	0.03	0.35	<.001	<.001	<.01	5.7
CMC 05-01	25526	39.10	40.60	1.50	<.01	1.16	0.06	0.001	0.27	0.79	0.06	0.3	<.001	<.001	<.01	3.01
CMC 05-01	25527	40.60	42.10	1.50	<.01	0.87	0.073	0.001	0.16	0.8	0.02	0.35	<.001	<.001	<.01	7.38
CMC 05-01	25528	42.10	43.60	1.50	<.01	0.47	0.073	0.001	0.1	0.78	<.01	0.38	<.001	<.001	<.01	6.15
CMC 05-01	25529	43.60	45.10	1.50	<.01	0.3	0.058	<.001	0.11	0.54	0.06	0.47	<.001	<.001	<.01	5.93
CMC 05-01	25530	45.10	46.60	1.50	<.01	0.48	0.072	0.001	0.19	0.92	0.03	0.32	<.001	<.001	0.01	5.83
CMC 05-01	25531	46.60	48.10	1.50	<.01	1.18	0.068	<.001	0.17	0.56	0.07	0.44	<.001	<.001	<.01	6.52
CMC 05-01	25532	48.10	49.60	1.50	<.01	1.51	0.066	0.001	0.25	0.57	0.01	0.33	<.001	<.001	<.01	5.67
CMC 05-01	25533	49.60	51.10	1.50	<.01	1.12	0.061	0.001	0.33	0.61	0.04	0.29	<.001	<.001	0.01	4.85

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-01	25534	51.10	52.90	1.80	<.001	0.001	0.01	0.04	<2	<.001	<.001	0.17	1.95	<.01	0.008	<.001	<.001
CMC 05-01	25958	52.90	54.40	1.50	<.001	0.003	<.01	0.02	<2	<.001	<.001	0.07	1.76	<.01	0.009	<.001	0.001
CMC 05-01	25959	54.40	55.90	1.50	<.001	0.001	<.01	0.03	<2	<.001	<.001	0.07	1.43	<.01	0.01	<.001	0.001
CMC 05-01	25960	55.90	57.60	1.70	<.001	0.002	<.01	0.08	<2	<.001	<.001	0.05	1.73	<.01	0.006	<.001	0.001
CMC 05-01	25535	57.60	58.56	0.96	0.001	0.006	0.08	1.41	10	<.001	<.001	0.71	2.89	0.02	0.001	0.005	0.001
CMC 05-01	25536	N/A	N/A	N/A	0.074	0.878	0.14	0.07	832	0.001	<.001	0.01	1.48	0.05	0.008	0.001	0.202
CMC 05-02	25537	17.59	18.34	0.75	0.001	0.002	<.01	0.14	<2	<.001	<.001	0.06	1.61	<.01	0.002	<.001	0.001
CMC 05-02	25961	18.34	19.12	0.78	0.001	0.004	0.02	0.17	<2	<.001	<.001	0.06	1.69	<.01	0.001	<.001	0.001
CMC 05-02	25962	19.12	20.12	1.00	0.001	0.001	0.01	0.25	<2	<.001	<.001	0.12	1.7	<.01	0.001	0.001	0.001
CMC 05-02	25963	20.12	21.12	1.00	<.001	0.002	<.01	0.17	<2	<.001	<.001	0.17	1.68	<.01	0.002	0.001	0.001
CMC 05-02	25964	21.12	22.12	1.00	0.001	0.004	0.06	0.38	6	<.001	<.001	0.55	2.74	<.01	0.002	0.002	<.001
CMC 05-02	25538	22.12	22.87	0.75	0.001	0.085	0.14	4.06	1013	<.001	0.001	1.26	6	<.01	<.001	0.021	0.031
CMC 05-02	25539	22.87	23.47	0.60	<.001	<.001	0.13	0.39	3	<.001	<.001	0.81	2.99	<.01	0.001	0.001	<.001
CMC 05-02	25540	23.47	23.92	0.45	0.002	0.814	0.37	25.99	5612	<.001	0.002	0.82	5.38	0.01	<.001	0.087	0.244
CMC 05-02	25541	23.92	24.70	0.78	<.001	0.003	0.01	0.42	23	<.001	<.001	0.09	0.96	<.01	0.002	0.001	0.004
CMC 05-02	25542	24.70	26.20	1.50	<.001	0.001	0.01	0.1	4	<.001	<.001	0.07	1.45	<.01	0.003	0.001	0.002
CMC 05-02	25543	26.20	27.70	1.50	<.001	0.004	<.01	0.16	22	<.001	<.001	0.07	1.63	<.01	0.003	0.001	0.002
CMC 05-02	25544	27.70	29.20	1.50	<.001	0.001	<.01	0.04	<2	<.001	<.001	0.05	2.05	<.01	0.005	<.001	<.001
CMC 05-02	25545	29.20	30.70	1.50	<.001	0.001	<.01	0.04	<2	<.001	<.001	0.04	2.34	<.01	0.004	<.001	<.001
CMC 05-02	25546	30.70	32.20	1.50	<.001	0.001	0.01	0.04	3	<.001	<.001	0.09	1.83	<.01	0.006	<.001	<.001
CMC 05-02	25547	32.20	33.70	1.50	<.001	<.001	<.01	0.03	<2	<.001	<.001	0.05	1.79	<.01	0.007	<.001	<.001
CMC 05-02	25548	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.11	<.01	0.004	<.001	<.001
CMC 05-02	25549	33.70	35.20	1.50	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.04	1.74	<.01	0.01	<.001	<.001
CMC 05-02	25550	35.20	36.61	1.41	<.001	0.001	0.01	0.02	<2	<.001	<.001	0.07	1.94	<.01	0.007	<.001	0.001
CMC 05-02	25551	N/A	N/A	N/A	0.075	0.887	0.14	0.08	854	<.001	<.001	0.01	1.47	0.05	0.008	0.001	0.204
CMC 05-02	25552	36.61	38.11	1.50	<.001	0.002	0.04	0.1	3	<.001	<.001	0.4	1.9	<.01	0.003	<.001	<.001
CMC 05-02	25553	38.11	38.61	0.50	0.001	0.046	0.48	5.75	238	<.001	<.001	3.18	9.91	0.01	0.001	0.015	0.012
CMC 05-02	25554	38.61	39.81	1.20	<.001	0.001	0.07	0.23	4	<.001	<.001	0.69	2.69	<.01	0.002	0.001	<.001
CMC 05-02	25555	38.61	39.81	1.20	<.001	<.001	0.06	0.17	2	<.001	<.001	0.63	2.5	<.01	0.002	0.001	<.001
CMC 05-03	25970	6.15	7.65	1.50	<.001	<.001	<.01	0.03	<2	<.001	<.001	0.04	0.63	<.01	0.128	<.001	<.001
CMC 05-03	25556	14.34	15.14	0.80	<.001	0.001	0.08	0.19	7	<.001	<.001	0.61	2.61	<.01	0.002	0.001	<.001
CMC 05-03	25557	15.14	16.08	0.94	<.001	0.005	0.11	0.97	8	<.001	<.001	1.13	4.14	<.01	0.001	0.004	<.001
CMC 05-03	25965	16.08	17.58	1.50	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.04	1.74	<.01	0.006	<.001	<.001
CMC 05-03	25966	17.58	19.08	1.50	<.001	<.001	<.01	0.03	<2	<.001	<.001	0.04	1.58	<.01	0.006	<.001	<.001
CMC 05-03	25967	19.08	20.80	1.72	<.001	0.001	<.01	0.02	<2	<.001	<.001	0.03	1.75	<.01	0.004	<.001	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-01	25534	51.10	52.90	1.80	<.01	1.3	0.06	0.001	0.3	0.67	0.02	0.34	<.001	<.001	0.01	6.7
CMC 05-01	25958	52.90	54.40	1.50	<.01	1.58	0.063	<.001	0.25	0.81	0.01	0.28	0.001	<.001	<.01	6.41
CMC 05-01	25959	54.40	55.90	1.50	<.01	1.91	0.061	0.001	0.22	0.89	0.01	0.25	0.001	<.001	<.01	6.32
CMC 05-01	25960	55.90	57.60	1.70	<.01	1.11	0.063	<.001	0.3	0.96	0.02	0.27	<.001	<.001	<.01	5.96
CMC 05-01	25535	57.60	58.56	0.96	<.01	0.25	0.052	<.001	0.09	0.5	0.01	0.47	<.001	<.001	0.01	2.72
CMC 05-01	25536	N/A	N/A	N/A	<.01	0.52	0.008	0.002	0.1	0.2	0.02	0.13	<.001	0.001	0.1	-
CMC 05-02	25537	17.59	18.34	0.75	<.01	0.49	0.068	<.001	0.12	0.71	<.01	0.33	<.001	<.001	0.01	2.7
CMC 05-02	25961	18.34	19.12	0.78	<.01	0.18	0.068	<.001	0.05	0.7	0.01	0.34	<.001	<.001	<.01	1.85
CMC 05-02	25962	19.12	20.12	1.00	<.01	0.38	0.068	<.001	0.06	0.62	<.01	0.4	0.001	<.001	<.01	3.76
CMC 05-02	25963	20.12	21.12	1.00	<.01	0.49	0.068	<.001	0.1	0.7	<.01	0.34	0.001	<.001	<.01	3.31
CMC 05-02	25964	21.12	22.12	1.00	<.01	0.44	0.068	<.001	0.13	0.65	<.01	0.41	<.001	<.001	<.01	4.46
CMC 05-02	25538	22.12	22.87	0.75	<.01	0.19	0.045	<.001	0.16	0.61	<.01	0.33	<.001	<.001	0.1	2.14
CMC 05-02	25539	22.87	23.47	0.60	<.01	0.26	0.066	<.001	0.11	0.5	<.01	0.44	<.001	<.001	0.01	1.8
CMC 05-02	25540	23.47	23.92	0.45	<.01	0.07	0.012	<.001	0.06	0.16	<.01	0.12	<.001	0.001	0.25	1.78
CMC 05-02	25541	23.92	24.70	0.78	<.01	0.38	0.07	0.001	0.07	0.67	0.01	0.2	<.001	<.001	<.01	2.62
CMC 05-02	25542	24.70	26.20	1.50	<.01	0.73	0.069	0.001	0.15	0.56	<.01	0.29	<.001	<.001	<.01	4.58
CMC 05-02	25543	26.20	27.70	1.50	<.01	0.67	0.068	0.001	0.17	0.69	0.01	0.26	<.001	<.001	<.01	5.62
CMC 05-02	25544	27.70	29.20	1.50	<.01	1.01	0.07	0.001	0.38	1.12	0.02	0.3	0.001	<.001	<.01	5.22
CMC 05-02	25545	29.20	30.70	1.50	<.01	0.75	0.067	0.001	0.48	1.33	0.03	0.42	<.001	<.001	<.01	5.61
CMC 05-02	25546	30.70	32.20	1.50	<.01	1.15	0.068	0.001	0.31	0.86	0.01	0.3	<.001	<.001	<.01	5.88
CMC 05-02	25547	32.20	33.70	1.50	<.01	1.4	0.065	0.001	0.37	0.89	0.03	0.34	<.001	<.001	<.01	4.13
CMC 05-02	25548	N/A	N/A	N/A	<.01	19.51	0.001	<.001	12.11	0.03	<.01	0.01	<.001	<.001	<.01	2.79
CMC 05-02	25549	33.70	35.20	1.50	<.01	1.46	0.067	0.001	0.36	0.78	0.03	0.32	<.001	<.001	<.01	6.03
CMC 05-02	25550	35.20	36.61	1.41	<.01	1.48	0.071	0.001	0.3	0.86	0.01	0.37	<.001	<.001	<.01	4.72
CMC 05-02	25551	N/A	N/A	N/A	0.01	0.51	0.008	0.003	0.1	0.19	0.02	0.12	<.001	0.001	0.08	-
CMC 05-02	25552	36.61	38.11	1.50	<.01	0.84	0.072	<.001	0.19	0.51	<.01	0.4	<.001	<.001	<.01	5.59
CMC 05-02	25553	38.11	38.61	0.50	<.01	0.2	0.035	<.001	0.2	0.36	<.01	0.34	<.001	0.001	0.08	1.47
CMC 05-02	25554	38.61	39.81	1.20	<.01	0.64	0.069	<.001	0.19	0.44	0.01	0.42	<.001	<.001	<.01	4.65
CMC 05-02	25555	38.61	39.81	1.20	<.01	0.65	0.069	<.001	0.18	0.44	<.01	0.42	<.001	<.001	0.01	4.08
CMC 05-03	25970	6.15	7.65	1.50	<.01	30.07	0.119	<.001	0.07	0.15	0.01	0.03	<.001	<.001	<.01	6.36
CMC 05-03	25556	14.34	15.14	0.80	<.01	0.52	0.065	<.001	0.12	0.47	<.01	0.45	<.001	<.001	<.01	3.57
CMC 05-03	25557	15.14	16.08	0.94	<.01	0.24	0.047	<.001	0.11	0.4	<.01	0.39	<.001	<.001	<.01	3.75
CMC 05-03	25965	16.08	17.58	1.50	<.01	0.88	0.065	0.001	0.35	0.67	0.06	0.35	<.001	<.001	<.01	6.35
CMC 05-03	25966	17.58	19.08	1.50	<.01	0.94	0.067	0.001	0.28	0.72	0.04	0.38	<.001	<.001	0.01	5.49
CMC 05-03	25967	19.08	20.80	1.72	<.01	0.67	0.065	0.001	0.35	0.85	0.06	0.37	0.022	<.001	<.01	6.28

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-03	25558	20.80	22.30	1.50	<.001	<.001	0.03	0.19	<2	<.001	<.001	0.3	1.96	<.01	0.001	0.001	<.001
CMC 05-03	25559	22.30	22.75	0.45	0.001	0.125	12.61	1.77	1663	<.001	<.001	0.64	2.78	<.01	0.001	0.008	0.136
CMC 05-03	25560	22.75	24.25	1.50	<.001	<.001	0.02	0.09	2	<.001	<.001	0.08	1.64	<.01	0.004	<.001	0.001
CMC 05-03	25968	24.25	26.25	2.00	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.03	1.8	<.01	0.004	<.001	<.001
CMC 05-03	25969	26.25	27.90	1.65	<.001	0.003	0.01	0.03	<2	<.001	<.001	0.05	1.95	<.01	0.004	<.001	<.001
CMC 05-03	25561	27.90	28.90	1.00	<.001	0.001	0.01	0.19	<2	<.001	<.001	0.11	2.23	<.01	0.002	0.001	<.001
CMC 05-03	25562	40.50	41.50	1.00	0.001	0.001	0.06	0.07	7	<.001	<.001	0.18	1.7	<.01	0.003	<.001	<.001
CMC 05-03	25563	41.50	42.50	1.00	0.001	<.001	<.01	0.01	<2	<.001	<.001	0.08	1.27	<.01	0.004	<.001	<.001
CMC 05-03	25564	42.50	43.50	1.00	0.007	0.001	0.01	0.03	<2	<.001	<.001	0.12	1.6	<.01	0.004	<.001	<.001
CMC 05-03	25565	43.50	44.60	1.10	0.001	<.001	<.01	0.02	<2	<.001	0.001	0.05	1.46	<.01	0.001	<.001	<.001
CMC 05-04	25567	3.05	5.15	2.10	0.002	0.003	0.01	4.04	5	0.002	<.001	9.1	9.79	0.01	0.017	0.009	<.001
CMC 05-04	25568	5.15	6.15	1.00	<.001	0.001	0.03	1.11	2	<.001	<.001	1.01	1.4	<.01	0.08	0.002	<.001
CMC 05-04	25971	7.65	9.30	1.65	<.001	<.001	<.01	0.02	<2	0.001	<.001	0.02	0.73	<.01	0.127	<.001	<.001
CMC 05-04	25972	7.65	9.30	1.65	<.001	<.001	<.01	0.03	<2	0.001	<.001	0.02	0.72	<.01	0.131	<.001	<.001
CMC 05-04	25569	9.30	10.30	1.00	<.001	<.001	<.01	0.03	<2	<.001	<.001	0.03	0.71	<.01	0.144	<.001	<.001
CMC 05-04	25570	10.30	11.00	0.70	0.003	0.002	<.01	0.81	<2	0.001	0.001	0.55	6.94	<.01	0.004	0.003	<.001
CMC 05-04	25571	11.00	12.50	1.50	0.007	<.001	<.01	1.16	<2	0.003	0.001	1.44	10.45	0.01	0.013	0.001	<.001
CMC 05-04	25572	12.50	14.00	1.50	0.006	0.002	0.02	1.07	8	0.003	0.001	1.47	8.84	0.01	0.01	0.003	0.001
CMC 05-04	25573	14.00	14.90	0.90	0.002	0.001	0.03	0.38	61	0.002	<.001	0.57	6.05	<.01	0.006	0.001	0.001
CMC 05-04	25574	14.90	18.00	3.10	0.006	0.004	0.15	2.15	77	0.001	<.001	1.79	7.41	<.01	0.008	0.006	0.004
CMC 05-04	25575	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.12	<.01	0.004	<.001	<.001
CMC 05-04	25576	18.00	19.00	1.00	0.01	0.005	0.57	2.35	108	0.001	<.001	3.61	4.12	0.01	0.014	0.007	0.005
CMC 05-04	25577	19.00	20.40	1.40	0.005	0.007	0.23	3.09	45	0.002	<.001	4.54	7.42	0.02	0.016	0.007	0.002
CMC 05-04	25578	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.09	<.01	0.004	<.001	<.001
CMC 05-04	25579	20.40	21.50	1.10	0.003	0.005	0.08	2.76	4	0.001	<.001	4.94	4.52	0.01	0.017	0.006	<.001
CMC 05-04	25580	21.50	22.50	1.00	0.004	0.007	0.05	4.48	8	0.001	<.001	5.26	5.39	0.01	0.019	0.01	<.001
CMC 05-04	25581	N/A	N/A	N/A	0.075	0.906	0.14	0.08	833	<.001	<.001	0.02	1.49	0.05	0.008	0.001	0.207
CMC 05-04	25582	22.50	23.50	1.00	0.001	0.004	0.02	1.8	4	0.001	<.001	4.11	3.91	0.01	0.022	0.004	<.001
CMC 05-04	25583	23.50	24.50	1.00	0.001	0.004	0.17	1.88	6	0.002	<.001	5.16	5.69	0.5	0.023	0.004	0.004
CMC 05-04	25584	24.50	25.20	0.70	0.001	0.003	0.18	2.14	5	0.001	<.001	3.59	2.66	0.08	0.038	0.005	0.001
CMC 05-04	25585	25.20	26.20	1.00	<.001	<.001	<.01	0.02	<2	<.001	<.001	0.1	0.31	<.01	0.196	<.001	<.001
CMC 05-04	25586	25.20	26.20	1.00	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.04	0.28	<.01	0.199	<.001	0.001
CMC 05-04	25973	N/A	N/A	N/A	0.078	0.893	0.14	0.08	819	<.001	<.001	0.01	1.45	0.05	0.008	0.001	0.204
CMC 05-04	25974	N/A	N/A	N/A	<.001	0.002	<.01	<.01	<2	<.001	<.001	0.01	0.1	<.01	0.005	<.001	<.001
CMC 05-04	25975	26.20	28.30	2.10	<.001	0.001	0.04	0.07	<2	<.001	<.001	0.17	0.52	<.01	0.177	<.001	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-03	25558	20.80	22.30	1.50	<.01	0.34	0.068	<.001	0.16	0.63	0.01	0.37	<.001	<.001	<.01	5.87
CMC 05-03	25559	22.30	22.75	0.45	<.01	0.18	0.049	<.001	0.1	0.53	<.01	0.43	<.001	<.001	0.14	1.22
CMC 05-03	25560	22.75	24.25	1.50	<.01	0.83	0.07	0.001	0.27	0.81	0.02	0.33	<.001	<.001	<.01	4.6
CMC 05-03	25968	24.25	26.25	2.00	<.01	0.63	0.066	0.001	0.41	0.8	0.06	0.34	<.001	<.001	<.01	6.56
CMC 05-03	25969	26.25	27.90	1.65	<.01	0.88	0.073	<.001	0.4	1.24	0.01	0.31	<.001	<.001	<.01	6.25
CMC 05-03	25561	27.90	28.90	1.00	<.01	0.28	0.07	0.001	0.33	1.19	0.02	0.38	<.001	<.001	<.01	3.58
CMC 05-03	25562	40.50	41.50	1.00	<.01	0.76	0.065	<.001	0.15	0.55	<.01	0.47	<.001	<.001	<.01	3.62
CMC 05-03	25563	41.50	42.50	1.00	<.01	1.08	0.079	<.001	0.18	0.53	<.01	0.42	<.001	<.001	<.01	4.07
CMC 05-03	25564	42.50	43.50	1.00	<.01	0.91	0.076	0.001	0.18	0.48	<.01	0.4	<.001	<.001	<.01	3.93
CMC 05-03	25565	43.50	44.60	1.10	<.01	0.3	0.081	<.001	0.09	0.76	<.01	0.14	<.001	<.001	0.01	3.94
CMC 05-04	25567	3.05	5.15	2.10	<.01	2.72	0.09	0.001	0.04	0.35	0.01	0.24	<.001	<.001	0.01	3.52
CMC 05-04	25568	5.15	6.15	1.00	<.01	23.1	0.086	<.001	0.05	0.21	0.01	0.11	<.001	<.001	<.01	3.43
CMC 05-04	25971	7.65	9.30	1.65	<.01	30.55	0.11	0.001	0.08	0.27	0.02	0.03	<.001	<.001	<.01	4.68
CMC 05-04	25972	7.65	9.30	1.65	<.01	31.39	0.115	<.001	0.13	0.26	0.02	0.03	0.001	<.001	<.01	4.48
CMC 05-04	25569	9.30	10.30	1.00	<.01	31.8	0.058	<.001	0.14	0.3	0.03	0.04	<.001	<.001	<.01	4.35
CMC 05-04	25570	10.30	11.00	0.70	0.11	11.64	0.038	0.002	0.22	2.55	<.01	0.01	0.035	<.001	0.33	2.99
CMC 05-04	25571	11.00	12.50	1.50	0.05	6.01	0.029	0.002	0.33	2.54	<.01	0.44	<.001	<.001	0.12	1.86
CMC 05-04	25572	12.50	14.00	1.50	0.01	7.78	0.039	0.002	0.25	2.13	0.01	0.3	0.021	<.001	0.04	1.42
CMC 05-04	25573	14.00	14.90	0.90	0.14	8.48	0.022	0.003	0.38	2.81	0.01	0.17	0.025	<.001	0.18	2.27
CMC 05-04	25574	14.90	18.00	3.10	0.04	13.82	0.031	0.003	0.11	1.48	<.01	0.09	<.001	<.001	0.07	3.14
CMC 05-04	25575	N/A	N/A	N/A	<.01	19.36	<.001	<.001	12.01	0.02	0.01	0.01	<.001	<.001	<.01	2.95
CMC 05-04	25576	18.00	19.00	1.00	0.07	12.95	0.064	0.001	0.05	0.21	<.01	0.14	<.001	<.001	0.16	3.52
CMC 05-04	25577	19.00	20.40	1.40	0.02	10.58	0.057	0.001	0.07	0.6	0.01	0.22	<.001	<.001	0.05	2.72
CMC 05-04	25578	N/A	N/A	N/A	<.01	21.4	0.001	<.001	11.87	0.01	<.01	0.01	<.001	<.001	<.01	3.18
CMC 05-04	25579	20.40	21.50	1.10	<.01	10.04	0.163	<.001	0.02	0.15	0.01	0.13	<.001	<.001	<.01	4.05
CMC 05-04	25580	21.50	22.50	1.00	<.01	12.48	0.083	<.001	0.04	0.21	<.01	0.17	<.001	<.001	<.01	3.72
CMC 05-04	25581	N/A	N/A	N/A	0.01	0.53	0.007	0.003	0.09	0.2	0.02	0.13	<.001	<.001	0.11	-
CMC 05-04	25582	22.50	23.50	1.00	<.01	15.42	0.071	<.001	0.03	0.13	<.01	0.11	<.001	<.001	<.01	3.96
CMC 05-04	25583	23.50	24.50	1.00	<.01	10.25	0.129	<.001	0.02	0.12	0.01	0.12	<.001	<.001	0.07	3.42
CMC 05-04	25584	24.50	25.20	0.70	<.01	22.71	0.139	<.001	0.04	0.17	<.01	0.14	<.001	<.001	0.01	3.16
CMC 05-04	25585	25.20	26.20	1.00	<.01	33.56	0.059	<.001	0.14	0.11	<.01	0.03	<.001	<.001	<.01	3.52
CMC 05-04	25586	25.20	26.20	1.00	<.01	31.78	0.046	0.001	0.13	0.12	0.01	0.02	<.001	<.001	<.01	4.03
CMC 05-04	25973	N/A	N/A	N/A	0.01	0.56	0.007	0.003	0.09	0.19	0.02	0.13	<.001	<.001	0.13	-
CMC 05-04	25974	N/A	N/A	N/A	<.01	20.48	0.002	<.001	11.85	0.01	0.01	0.01	<.001	<.001	<.01	6.55
CMC 05-04	25975	26.20	28.30	2.10	<.01	29.44	0.028	<.001	0.12	0.16	<.01	0.08	<.001	<.001	<.01	8.85

CMC METALS LTD

2005 ASSAY LOG
Holes CMC05-01 to CMC05-14

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-04	25587	28.31	28.81	0.50	<.001	0.001	<.01	0.01	<2	0.001	<.001	0.03	0.46	<.01	0.188	<.001	<.001
CMC 05-04	25588	28.81	29.40	0.59	0.009	0.011	0.42	3.79	16	0.014	<.001	7.48	6.07	0.06	0.06	0.01	<.001
CMC 05-04	25589	29.40	29.90	0.50	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.03	0.25	<.01	0.156	<.001	<.001
CMC 05-04	25590	29.90	30.35	0.45	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.27	<.01	0.122	<.001	<.001
CMC 05-04	25591	30.35	31.10	0.75	<.001	<.001	<.01	0.02	<2	<.001	<.001	0.03	0.25	<.01	0.097	<.001	<.001
CMC 05-04	25592	31.10	31.60	0.50	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.24	<.01	0.083	<.001	0.001
CMC 05-04	25976	31.60	33.10	1.50	<.001	0.001	<.01	0.02	<2	<.001	<.001	0.01	0.3	<.01	0.092	<.001	0.001
CMC 05-04	25977	33.10	34.50	1.40	<.001	0.001	<.01	0.02	<2	0.001	<.001	0.28	2.35	<.01	0.036	<.001	0.001
CMC 05-04	25593	34.50	35.00	0.50	<.001	0.004	<.01	0.01	<2	0.002	<.001	0.36	3.27	<.01	0.01	<.001	<.001
CMC 05-04	25594	35.00	35.95	0.95	0.003	0.013	<.01	0.01	<2	0.001	0.001	0.29	5.4	<.01	0.019	<.001	<.001
CMC 05-04	25595	35.95	36.90	0.95	0.007	0.01	<.01	<.01	<2	0.001	<.001	0.23	4.29	<.01	0.008	<.001	0.001
CMC 05-04	25596	36.90	37.40	0.50	<.001	0.04	<.01	0.01	<2	0.004	0.001	0.08	2.5	<.01	0.023	<.001	0.001
CMC 05-04	25597	37.40	38.80	1.40	<.001	0.003	<.01	0.01	<2	0.002	0.001	0.02	2.33	<.01	0.006	<.001	<.001
CMC 05-04	25598	38.80	40.30	1.50	<.001	0.002	<.01	0.01	<2	0.002	0.001	0.01	2.21	<.01	0.01	<.001	<.001
CMC 05-04	25599	40.30	41.80	1.50	<.001	0.004	<.01	0.01	<2	0.002	0.001	0.01	1.99	<.01	0.005	<.001	0.001
CMC 05-04	25600	41.80	43.30	1.50	<.001	0.002	<.01	<.01	<2	0.003	0.001	0.01	2.89	<.01	0.006	<.001	<.001
CMC 05-04	25601	43.30	43.40	0.10	0.014	0.011	0.82	2.5	207	0.004	0.001	4.2	12.72	0.04	0.039	0.01	0.002
CMC 05-04	25602	43.40	44.90	1.50	<.001	0.002	<.01	0.01	<2	0.003	0.001	0.02	2.4	<.01	0.006	<.001	<.001
CMC 05-04	25603	44.90	46.40	1.50	<.001	0.004	<.01	0.01	<2	0.003	0.001	0.02	2.46	<.01	0.01	<.001	<.001
CMC 05-04	25604	46.40	47.90	1.50	<.001	0.003	<.01	0.01	<2	0.003	0.001	0.03	3.21	<.01	0.01	<.001	<.001
CMC 05-04	25605	47.90	48.30	0.40	<.001	0.004	<.01	0.03	<2	0.004	0.002	0.05	4.46	<.01	0.014	<.001	<.001
CMC 05-04	25606	48.30	49.28	0.98	0.002	0.003	0.07	1.77	6	0.002	0.001	1.37	4.33	0.04	0.006	0.002	<.001
CMC 05-04	25607	49.28	49.72	0.44	0.007	0.012	0.03	3.04	21	0.001	<.001	6.78	17.96	0.16	0.017	0.006	<.001
CMC 05-04	25608	49.72	50.16	0.44	0.005	0.004	0.04	2.03	5	0.001	<.001	7.93	21.37	0.09	0.01	0.005	<.001
CMC 05-04	25609	50.16	50.60	0.44	0.015	0.005	0.14	2.53	17	0.001	0.001	10.22	19.61	0.22	0.02	0.008	<.001
CMC 05-04	25610	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.13	<.01	0.004	<.001	<.001
CMC 05-04	25611	50.60	51.07	0.47	0.003	0.011	0.09	1.99	13	0.001	<.001	9.62	20.83	0.06	0.008	0.006	<.001
CMC 05-04	25612	51.07	51.54	0.47	0.002	0.011	0.04	1.85	14	0.001	<.001	12.89	25.04	0.07	0.008	0.007	<.001
CMC 05-04	25613	51.54	52.01	0.47	0.002	0.007	0.04	1.84	4	0.001	<.001	8.56	17.22	0.05	0.005	0.007	<.001
CMC 05-04	25614	N/A	N/A	N/A	0.076	0.885	0.14	0.08	835	<.001	<.001	0.02	1.51	0.05	0.008	0.001	0.206
CMC 05-04	25615	52.01	52.44	0.43	0.008	0.06	0.16	2.24	88	0.001	<.001	6.07	16.99	0.06	0.008	0.014	0.002
CMC 05-04	25616	52.44	52.87	0.43	0.006	0.092	0.05	2.3	192	0.001	<.001	6.6	16.77	0.14	0.01	0.013	0.003
CMC 05-04	25617	52.87	53.30	0.43	0.008	0.108	0.04	4.18	138	0.001	<.001	5.74	14.89	0.23	0.011	0.027	0.011
CMC 05-04	25618	53.30	53.95	0.65	<.001	0.007	0.06	1.39	3	0.003	0.001	1.83	7.03	0.09	0.002	0.006	0.001
CMC 05-04	25619	53.95	54.60	0.65	0.007	0.007	0.14	2.62	7	0.004	0.001	1.87	7.23	0.07	0.004	0.005	0.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-04	25587	28.31	28.81	0.50	<.01	31.85	0.023	0.001	0.07	0.18	<.01	0.06	0.001	<.001	<.01	1.65
CMC 05-04	25588	28.81	29.40	0.59	<.01	7.06	0.45	0.001	0.08	0.5	0.01	0.23	<.001	<.001	0.01	0.48
CMC 05-04	25589	29.40	29.90	0.50	<.01	34	0.024	<.001	0.16	0.06	<.01	0.02	<.001	<.001	<.01	1.66
CMC 05-04	25590	29.90	30.35	0.45	<.01	33.34	0.019	<.001	0.2	0.06	<.01	0.03	<.001	<.001	<.01	1.47
CMC 05-04	25591	30.35	31.10	0.75	<.01	33.69	0.017	<.001	0.17	0.05	<.01	0.02	0.001	<.001	<.01	0.81
CMC 05-04	25592	31.10	31.60	0.50	<.01	34.38	0.019	<.001	0.25	0.04	<.01	0.02	<.001	<.001	<.01	1.65
CMC 05-04	25976	31.60	33.10	1.50	<.01	33.33	0.021	<.001	0.29	0.06	<.01	0.03	0.001	<.001	<.01	6.38
CMC 05-04	25977	33.10	34.50	1.40	<.01	16.17	0.021	0.002	0.32	1.66	<.01	0.02	0.011	<.001	0.01	6.76
CMC 05-04	25593	34.50	35.00	0.50	0.01	9.59	0.017	0.003	0.45	2.45	0.01	<.01	0.002	<.001	0.01	1.79
CMC 05-04	25594	35.00	35.95	0.95	0.01	8.08	0.066	0.002	0.61	1.43	<.01	<.01	0.087	<.001	0.08	3.66
CMC 05-04	25595	35.95	36.90	0.95	0.01	8.76	0.019	0.001	0.25	1.04	<.01	<.01	0.081	<.001	0.06	4.04
CMC 05-04	25596	36.90	37.40	0.50	<.01	3.56	0.028	0.005	0.57	3.08	0.29	0.22	0.006	<.001	0.01	1.98
CMC 05-04	25597	37.40	38.80	1.40	<.01	2.09	0.015	0.003	0.41	1.14	0.07	0.12	0.003	<.001	<.01	5.43
CMC 05-04	25598	38.80	40.30	1.50	<.01	1.68	0.016	0.003	0.3	1	0.09	0.16	0.001	<.001	<.01	6.17
CMC 05-04	25599	40.30	41.80	1.50	<.01	1.48	0.012	0.003	0.28	0.6	0.07	0.1	0.002	<.001	<.01	6.02
CMC 05-04	25600	41.80	43.30	1.50	<.01	1.45	0.018	0.003	0.44	1.19	0.09	0.27	<.001	<.001	<.01	5.57
CMC 05-04	25601	43.30	43.40	0.10	0.06	10.08	0.07	0.001	0.09	0.58	0.01	0.23	0.01	<.001	0.11	1.21
CMC 05-04	25602	43.40	44.90	1.50	<.01	1.82	0.016	0.003	0.42	0.93	0.06	0.26	<.001	<.001	<.01	5.75
CMC 05-04	25603	44.90	46.40	1.50	<.01	4.39	0.015	0.003	0.3	2.07	0.05	0.1	<.001	<.001	0.01	5.99
CMC 05-04	25604	46.40	47.90	1.50	<.01	2.85	0.019	0.003	0.66	2.01	0.13	0.24	0.001	<.001	<.01	6.65
CMC 05-04	25605	47.90	48.30	0.40	<.01	3.69	0.025	0.004	0.75	2.29	0.16	0.36	<.001	<.001	<.01	1.92
CMC 05-04	25606	48.30	49.28	0.98	<.01	1.82	0.015	0.001	0.18	1.51	0.01	0.35	0.001	<.001	<.01	3.59
CMC 05-04	25607	49.28	49.72	0.44	<.01	0.12	0.012	<.001	0.01	0.38	0.01	0.11	0.003	<.001	0.01	1.68
CMC 05-04	25608	49.72	50.16	0.44	<.01	0.08	0.01	<.001	0.02	0.1	0.01	0.07	0.003	<.001	0.01	1.68
CMC 05-04	25609	50.16	50.60	0.44	<.01	0.09	0.026	<.001	<.01	0.12	0.01	0.09	0.004	<.001	<.01	1.78
CMC 05-04	25610	N/A	N/A	N/A	<.01	21.12	0.001	<.001	11.73	0.01	<.01	0.01	0.001	<.001	<.01	4.05
CMC 05-04	25611	50.60	51.07	0.47	<.01	0.09	0.01	<.001	0.07	0.13	0.01	0.1	0.002	<.001	0.01	1.96
CMC 05-04	25612	51.07	51.54	0.47	<.01	0.14	0.013	<.001	0.16	0.09	0.01	0.07	0.003	0.001	0.01	1.69
CMC 05-04	25613	51.54	52.01	0.47	<.01	0.13	0.011	<.001	0.15	0.18	<.01	0.12	0.002	<.001	0.01	2.08
CMC 05-04	25614	N/A	N/A	N/A	<.01	0.5	0.008	0.003	0.09	0.2	0.02	0.13	<.001	<.001	0.1	-
CMC 05-04	25615	52.01	52.44	0.43	<.01	0.37	0.013	<.001	0.12	0.38	<.01	0.19	0.004	<.001	0.01	1.59
CMC 05-04	25616	52.44	52.87	0.43	<.01	0.13	0.017	0.001	0.06	0.47	0.01	0.28	0.003	<.001	0.03	1.62
CMC 05-04	25617	52.87	53.30	0.43	<.01	0.13	0.015	<.001	0.01	0.5	0.01	0.31	0.008	<.001	0.13	2.03
CMC 05-04	25618	53.30	53.95	0.65	<.01	0.21	0.07	0.001	0.15	0.88	<.01	0.47	0.001	<.001	0.01	2.52
CMC 05-04	25619	53.95	54.60	0.65	<.01	0.64	0.088	0.002	0.14	1.2	<.01	0.63	0.002	<.001	0.01	3.18

CMC METALS LTD

2005 ASSAY LOG
Holes CMC05-01 to CMC05-14

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-04	25620	54.60	55.43	0.83	0.008	0.003	<.01	2.81	<2	0.006	0.002	1.11	4.19	0.03	0.004	0.002	<.001
CMC 05-04	25621	55.43	56.25	0.82	0.002	0.005	<.01	0.71	<2	0.004	0.001	0.3	3.77	0.02	0.002	<.001	0.002
CMC 05-04	25622	56.25	57.25	1.00	<.001	0.007	<.01	0.14	<2	0.005	0.001	0.14	4.03	<.01	0.012	<.001	<.001
CMC 05-04	25623	56.25	57.25	1.00	<.001	0.008	<.01	0.13	<2	0.005	0.002	0.13	4.08	<.01	0.012	<.001	0.001
CMC 05-05	25624	4.57	5.56	0.99	<.001	0.026	<.01	0.06	<2	0.003	0.001	0.11	3.3	<.01	0.017	<.001	0.001
CMC 05-05	25625	5.56	6.55	0.99	<.001	0.002	<.01	0.01	<2	0.002	<.001	0.16	2.57	<.01	0.023	<.001	0.001
CMC 05-05	25626	6.55	7.54	0.99	<.001	0.006	<.01	<.01	<2	0.004	0.001	0.07	3.93	<.01	0.014	<.001	<.001
CMC 05-05	25627	7.54	8.53	0.99	<.001	0.007	<.01	<.01	<2	0.005	0.002	0.03	3.86	<.01	0.007	<.001	<.001
CMC 05-05	25628	8.53	9.52	0.99	<.001	0.009	<.01	<.01	<2	0.003	0.001	0.02	3.19	<.01	0.008	<.001	<.001
CMC 05-05	25629	9.52	10.51	0.99	<.001	0.012	<.01	<.01	<2	0.005	0.002	0.03	4.44	<.01	0.005	<.001	<.001
CMC 05-05	25630	10.51	11.50	0.99	<.001	0.004	<.01	<.01	<2	0.004	0.001	0.03	3.33	<.01	0.006	<.001	<.001
CMC 05-05	25631	11.50	12.50	1.00	0.001	0.001	<.01	0.02	<2	0.003	0.001	0.24	3.13	<.01	0.023	<.001	<.001
CMC 05-05	25632	12.50	13.49	0.99	0.001	0.001	<.01	0.02	<2	0.003	0.001	0.27	3.26	<.01	0.022	<.001	0.001
CMC 05-05	25633	13.49	14.48	0.99	<.001	0.001	<.01	0.09	<2	0.002	<.001	0.32	3.63	<.01	0.038	<.001	<.001
CMC 05-05	25634	14.48	15.47	0.99	0.001	0.011	<.01	0.2	<2	0.004	0.001	0.11	4.58	<.01	0.009	<.001	0.001
CMC 05-05	25635	15.47	16.46	0.99	0.002	0.012	<.01	0.36	<2	0.003	<.001	0.03	4.43	<.01	0.001	<.001	<.001
CMC 05-05	25636	16.46	17.45	0.99	0.006	0.081	<.01	1.38	<2	0.003	0.003	0.63	3.99	0.04	0.003	0.001	<.001
CMC 05-05	25637	17.45	18.44	0.99	0.018	0.056	<.01	1.53	<2	0.006	0.003	2.51	4.17	0.11	0.01	0.002	0.002
CMC 05-05	25638	18.44	19.43	0.99	0.041	0.006	<.01	1.13	<2	0.005	0.002	1.6	4.98	0.1	0.005	0.002	0.001
CMC 05-05	25639	19.43	20.42	0.99	0.012	0.018	0.11	3.96	8	0.005	0.002	2.69	6.01	0.11	0.008	0.004	0.002
CMC 05-05	25640	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.09	<.01	0.004	<.001	<.001
CMC 05-05	25641	20.42	21.41	0.99	0.007	0.033	0.44	1.46	43	0.002	<.001	3.33	12.44	0.25	0.007	0.006	0.003
CMC 05-05	25642	21.41	22.40	0.99	0.001	0.022	0.08	0.99	53	<.001	<.001	0.47	6.65	0.11	0.001	0.003	0.002
CMC 05-05	25643	22.40	23.39	0.99	<.001	0.014	0.01	0.84	3	<.001	<.001	0.23	3.99	0.06	0.001	0.002	<.001
CMC 05-05	25644	23.39	24.38	0.99	<.001	0.008	0.01	0.33	6	<.001	<.001	0.05	3.74	0.02	0.001	<.001	0.001
CMC 05-05	25645	N/A	N/A	N/A	0.074	0.847	0.15	0.09	791	<.001	<.001	0.02	1.47	0.05	0.008	0.001	0.194
CMC 05-05	25646	24.38	25.37	0.99	<.001	0.014	0.1	0.71	51	0.001	<.001	1.2	8.45	0.04	0.001	0.001	0.001
CMC 05-05	25647	25.37	26.36	0.99	0.001	0.005	0.18	2.36	14	0.003	0.001	2.91	11.29	0.1	0.002	0.005	0.001
CMC 05-05	25648	26.36	27.35	0.99	0.001	0.005	<.01	1.91	<2	0.005	0.001	0.69	3.34	0.03	0.003	0.002	<.001
CMC 05-05	25649	27.35	28.30	0.95	0.001	0.004	0.05	1.97	2	0.002	<.001	0.93	4.95	0.08	0.003	0.003	<.001
CMC 05-05	25650	28.30	28.80	0.50	<.001	<.001	0.43	3.13	12	0.002	<.001	4.61	13.86	0.05	0.004	0.007	<.001
CMC 05-05	25651	28.80	29.30	0.50	0.001	0.006	0.07	1.83	16	<.001	<.001	7.35	25.84	0.05	0.005	0.008	0.001
CMC 05-05	25652	29.30	29.80	0.50	0.003	0.005	0.08	2.92	13	<.001	<.001	8.61	33.68	0.16	0.014	0.009	0.001
CMC 05-05	25653	29.80	30.30	0.50	<.001	0.009	0.1	1.33	21	<.001	0.001	3.24	14.13	0.14	0.006	0.004	0.002
CMC 05-05	25654	30.30	31.32	1.02	<.001	0.005	0.29	0.71	15	0.001	<.001	1.25	6.65	0.12	0.001	0.002	0.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-04	25620	54.60	55.43	0.83	<.01	3.24	0.076	0.003	0.54	2.23	<.01	0.34	0.002	<.001	0.01	3.41
CMC 05-04	25621	55.43	56.25	0.82	<.01	0.78	0.041	0.003	0.39	1.33	<.01	0.52	0.001	<.001	<.01	2.82
CMC 05-04	25622	56.25	57.25	1.00	<.01	4.94	0.068	0.005	0.84	2.18	<.01	0.48	0.001	<.001	<.01	9.89
CMC 05-04	25623	56.25	57.25	1.00	<.01	4.63	0.056	0.005	0.84	2.14	<.01	0.47	0.001	<.001	0.01	10.18
CMC 05-05	25624	4.57	5.56	0.99	<.01	2.31	0.055	0.004	0.61	3.44	0.3	0.36	0.024	<.001	<.01	6.72
CMC 05-05	25625	5.56	6.55	0.99	<.01	4.47	0.061	0.002	0.18	2.57	0.13	0.09	0.011	<.001	0.01	4.83
CMC 05-05	25626	6.55	7.54	0.99	<.01	1.63	0.06	0.007	1.06	3.13	0.18	0.6	<.001	<.001	0.01	4.51
CMC 05-05	25627	7.54	8.53	0.99	<.01	1.22	0.043	0.007	1.06	2.44	0.1	0.38	<.001	<.001	0.01	5.1
CMC 05-05	25628	8.53	9.52	0.99	<.01	1.01	0.047	0.005	0.64	1.81	0.15	0.29	<.001	<.001	0.01	4.83
CMC 05-05	25629	9.52	10.51	0.99	<.01	0.73	0.049	0.006	1.07	2.38	0.08	0.28	<.001	<.001	<.01	3.74
CMC 05-05	25630	10.51	11.50	0.99	<.01	0.79	0.041	0.007	0.95	1.95	0.15	0.56	<.001	<.001	0.01	4.96
CMC 05-05	25631	11.50	12.50	1.00	<.01	6.66	0.056	0.003	0.66	2.13	0.08	0.35	<.001	<.001	<.01	4.25
CMC 05-05	25632	12.50	13.49	0.99	<.01	7.09	0.059	0.003	0.55	1.89	<.01	0.25	<.001	<.001	0.01	1.75
CMC 05-05	25633	13.49	14.48	0.99	<.01	9.91	0.046	0.002	0.14	0.94	<.01	0.28	<.001	<.001	0.01	1.62
CMC 05-05	25634	14.48	15.47	0.99	<.01	2.79	0.079	0.005	0.78	1.7	<.01	0.43	<.001	<.001	0.01	1.96
CMC 05-05	25635	15.47	16.46	0.99	<.01	0.19	0.037	0.006	1.15	2.09	<.01	0.45	0.001	<.001	<.01	2.21
CMC 05-05	25636	16.46	17.45	0.99	<.01	0.33	0.045	0.003	0.42	1.46	<.01	0.29	0.001	<.001	0.03	2.26
CMC 05-05	25637	17.45	18.44	0.99	<.01	0.35	0.046	0.003	0.21	1.12	<.01	0.3	0.001	<.001	<.01	2.15
CMC 05-05	25638	18.44	19.43	0.99	<.01	0.34	0.042	0.004	0.43	1.56	<.01	0.24	0.001	<.001	0.02	2.22
CMC 05-05	25639	19.43	20.42	0.99	<.01	0.29	0.038	0.003	0.29	1.26	<.01	0.39	0.004	<.001	0.02	3.43
CMC 05-05	25640	N/A	N/A	N/A	<.01	22.44	0.006	<.001	12.59	0.03	<.01	0.01	<.001	<.001	0.01	3.88
CMC 05-05	25641	20.42	21.41	0.99	<.01	0.12	0.021	0.001	0.04	0.82	<.01	0.5	0.001	<.001	0.04	4.69
CMC 05-05	25642	21.41	22.40	0.99	<.01	0.1	0.033	0.001	0.03	0.55	<.01	0.48	0.001	<.001	0.01	4.65
CMC 05-05	25643	22.40	23.39	0.99	<.01	0.04	0.042	0.001	0.03	0.66	<.01	0.51	0.001	<.001	0.01	4.46
CMC 05-05	25644	23.39	24.38	0.99	<.01	0.07	0.039	0.001	0.03	0.78	<.01	0.5	<.001	<.001	0.01	5.61
CMC 05-05	25645	N/A	N/A	N/A	0.01	0.52	0.004	0.003	0.09	0.2	0.02	0.17	<.001	0.001	0.09	-
CMC 05-05	25646	24.38	25.37	0.99	<.01	0.09	0.032	0.001	0.07	0.64	<.01	0.49	<.001	<.001	0.02	3.41
CMC 05-05	25647	25.37	26.36	0.99	<.01	0.74	0.069	0.002	0.34	1.3	<.01	0.51	0.001	<.001	0.01	4.55
CMC 05-05	25648	26.36	27.35	0.99	<.01	3.08	0.045	0.004	0.97	2.71	<.01	0.31	0.002	<.001	0.01	5.08
CMC 05-05	25649	27.35	28.30	0.95	<.01	4.13	0.047	0.003	0.5	2.13	<.01	0.39	0.003	<.001	<.01	5.15
CMC 05-05	25650	28.30	28.80	0.50	<.01	1.09	0.036	0.001	0.21	1.21	<.01	0.62	0.003	<.001	<.01	2.97
CMC 05-05	25651	28.80	29.30	0.50	<.01	0.09	0.038	0.001	0.01	0.34	<.01	0.27	0.001	<.001	0.01	3.16
CMC 05-05	25652	29.30	29.80	0.50	<.01	0.1	0.051	<.001	0.04	0.24	<.01	0.14	0.001	<.001	0.02	3.21
CMC 05-05	25653	29.80	30.30	0.50	<.01	0.06	0.031	0.001	0.03	0.84	<.01	0.43	0.001	<.001	0.02	1.81
CMC 05-05	25654	30.30	31.32	1.02	<.01	0.08	0.038	0.001	0.06	0.61	<.01	0.41	<.001	<.001	0.02	4.86

CMC METALS LTD

2005 ASSAY LOG
Holes CMC05-01 to CMC05-14

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-05	25655	31.32	32.34	1.02	<.001	0.005	0.08	0.89	5	0.002	0.001	0.72	4.57	0.01	0.001	0.001	<.001
CMC 05-05	25656	32.34	33.36	1.02	<.001	0.009	0.05	0.37	5	0.001	<.001	0.42	4.65	0.01	0.001	0.001	0.001
CMC 05-05	25657	32.34	33.36	1.02	<.001	0.008	0.05	0.41	4	0.001	<.001	0.3	5.01	0.01	0.001	<.001	<.001
CMC 05-05	25658	33.36	34.38	1.02	<.001	0.003	0.08	0.52	3	0.002	0.001	0.91	4.91	<.01	0.001	0.001	0.001
CMC 05-05	25659	34.38	35.40	1.02	0.001	0.001	0.09	0.9	<2	0.004	0.001	1.16	8.33	0.01	0.001	0.001	0.001
CMC 05-05	25660	35.40	36.42	1.02	0.001	0.001	0.03	0.81	<2	0.003	0.002	0.93	6.88	0.02	0.003	0.001	<.001
CMC 05-05	25661	36.42	37.95	1.53	0.001	0.003	0.1	0.55	4	0.001	0.001	0.68	5.62	0.01	0.002	<.001	0.001
CMC 05-05	25662	37.95	39.48	1.53	0.001	0.012	0.05	0.33	2	0.001	<.001	0.34	3.47	<.01	0.002	<.001	0.001
CMC 05-05	25663	39.48	40.50	1.02	0.001	0.016	0.08	0.32	9	0.001	<.001	0.13	4.71	0.05	0.001	<.001	0.001
CMC 05-05	25664	40.50	41.02	0.52	0.001	0.004	0.04	0.4	3	0.002	<.001	0.32	4.73	0.01	0.001	<.001	0.001
CMC 05-05	25665	41.02	41.54	0.52	0.001	0.002	0.03	0.24	<2	<.001	<.001	0.27	2.95	0.01	0.002	<.001	<.001
CMC 05-05	25666	41.54	42.06	0.52	0.01	0.013	<.01	0.8	<2	0.002	0.001	1.2	15.55	0.04	0.005	<.001	0.003
CMC 05-05	25667	42.06	42.58	0.52	0.002	0.003	<.01	0.71	<2	0.001	<.001	0.54	12.32	0.01	0.011	<.001	0.002
CMC 05-05	25668	42.58	43.10	0.52	0.003	0.006	<.01	1.11	<2	0.003	0.001	0.88	11.3	0.02	0.01	0.001	0.001
CMC 05-05	25669	43.10	43.60	0.50	0.005	0.008	<.01	0.65	<2	0.002	<.001	1.45	12.24	0.07	0.005	0.001	0.002
CMC 05-05	25670	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.18	<.01	0.004	<.001	<.001
CMC 05-05	25671	43.60	44.40	0.80	0.015	0.005	0.06	0.66	6	0.001	<.001	3.1	10.93	0.32	0.011	0.003	0.004
CMC 05-05	25672	44.40	45.20	0.80	0.005	0.005	0.13	0.93	10	0.001	0.001	3.19	14.37	1.11	0.015	0.005	0.006
CMC 05-05	25673	45.20	46.20	1.00	0.001	0.001	0.04	0.05	3	<.001	<.001	0.05	0.97	0.01	0.002	<.001	<.001
CMC 05-05	25978	46.20	47.70	1.50	<.001	0.001	0.01	0.03	3	<.001	<.001	0.01	0.82	0.01	0.001	<.001	<.001
CMC 05-05	25979	47.70	49.00	1.30	0.001	<.001	0.01	0.04	<2	<.001	<.001	0.03	0.8	<.01	0.002	<.001	0.001
CMC 05-05	25674	49.00	50.00	1.00	<.001	<.001	0.03	0.04	<2	<.001	<.001	0.04	0.87	<.01	0.005	<.001	<.001
CMC 05-05	25675	50.00	51.20	1.20	0.001	<.001	<.01	<.01	<2	<.001	<.001	0.04	0.91	<.01	0.006	<.001	0.001
CMC 05-06	25676	4.90	6.50	1.60	0.001	0.005	<.01	0.59	10	0.002	0.001	0.87	4.22	0.01	0.005	0.001	<.001
CMC 05-06	25677	N/A	N/A	N/A	0.075	0.856	0.15	0.09	821	0.001	<.001	0.02	1.46	0.05	0.008	0.001	0.193
CMC 05-06	25678	6.50	8.00	1.50	0.002	0.002	<.01	1.25	<2	0.003	0.001	0.61	3.87	<.01	0.007	0.001	0.001
CMC 05-06	25679	8.00	9.50	1.50	0.002	0.009	<.01	1.82	<2	0.005	0.002	0.62	3.94	0.01	0.002	0.001	<.001
CMC 05-06	25680	9.50	11.00	1.50	0.002	0.01	0.01	1.4	3	0.003	0.002	0.41	4.14	<.01	0.001	0.001	<.001
CMC 05-06	25681	11.00	12.50	1.50	0.001	0.004	<.01	0.78	<2	0.002	0.001	0.1	5.03	0.01	0.001	0.001	0.001
CMC 05-06	25682	12.50	14.00	1.50	<.001	0.004	<.01	0.41	<2	0.003	0.001	0.04	4.07	<.01	0.001	<.001	0.001
CMC 05-06	25683	14.00	15.50	1.50	<.001	0.003	<.01	0.39	<2	0.001	<.001	0.06	3.66	0.01	0.001	<.001	0.001
CMC 05-06	25684	14.00	15.50	1.50	<.001	0.003	<.01	0.39	<2	0.001	<.001	0.09	3.43	0.01	0.001	<.001	0.001
CMC 05-06	25685	15.50	17.00	1.50	<.001	0.005	<.01	0.38	<2	0.002	0.001	0.08	3.45	<.01	0.003	0.001	<.001
CMC 05-06	25686	17.00	18.50	1.50	<.001	0.004	<.01	1.04	3	0.003	0.003	0.42	3.77	0.01	0.003	0.002	0.001
CMC 05-06	25687	18.50	20.00	1.50	<.001	0.009	<.01	1.4	<2	0.003	0.001	0.24	3.48	<.01	0.002	0.004	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-05	25655	31.32	32.34	1.02	<.01	0.08	0.046	0.001	0.04	0.81	0.03	0.49	0.001	<.001	0.02	3.96
CMC 05-05	25656	32.34	33.36	1.02	<.01	0.09	0.046	0.001	0.05	0.76	<.01	0.51	<.001	<.001	0.03	4.29
CMC 05-05	25657	32.34	33.36	1.02	<.01	0.06	0.048	0.001	0.04	0.84	<.01	0.5	<.001	<.001	0.02	4.76
CMC 05-05	25658	33.36	34.38	1.02	<.01	0.14	0.045	0.001	0.09	0.69	<.01	0.35	<.001	<.001	0.02	4.91
CMC 05-05	25659	34.38	35.40	1.02	<.01	0.65	0.06	0.003	0.42	1.86	<.01	0.35	0.001	<.001	0.01	4.83
CMC 05-05	25660	35.40	36.42	1.02	<.01	3.89	0.055	0.003	0.43	2.46	<.01	0.33	0.001	<.001	<.01	5.31
CMC 05-05	25661	36.42	37.95	1.53	<.01	0.13	0.036	0.002	0.03	0.91	<.01	0.51	0.001	<.001	<.01	6.29
CMC 05-05	25662	37.95	39.48	1.53	<.01	0.12	0.038	0.001	0.03	0.92	<.01	0.5	<.001	<.001	0.01	7.62
CMC 05-05	25663	39.48	40.50	1.02	<.01	0.1	0.037	0.001	0.02	0.87	<.01	0.36	<.001	<.001	0.03	4.79
CMC 05-05	25664	40.50	41.02	0.52	<.01	0.18	0.062	0.001	0.03	1.18	<.01	0.56	0.001	<.001	0.02	3.05
CMC 05-05	25665	41.02	41.54	0.52	<.01	0.11	0.044	0.001	0.03	0.85	<.01	0.38	<.001	<.001	0.01	3
CMC 05-05	25666	41.54	42.06	0.52	<.01	1.78	0.224	0.002	0.06	1.74	<.01	0.11	0.003	<.001	0.01	3.96
CMC 05-05	25667	42.06	42.58	0.52	<.01	3.04	0.969	0.004	0.1	2.99	<.01	0.21	0.001	<.001	<.01	3.02
CMC 05-05	25668	42.58	43.10	0.52	<.01	4.73	0.946	0.003	0.23	2.55	<.01	0.13	0.002	<.001	0.01	2.25
CMC 05-05	25669	43.10	43.60	0.50	<.01	0.31	0.146	0.002	0.05	1.44	<.01	0.12	<.001	<.001	0.02	1.81
CMC 05-05	25670	N/A	N/A	N/A	<.01	22.59	0.01	<.001	12.64	0.05	<.01	<.01	<.001	<.001	<.01	3.53
CMC 05-05	25671	43.60	44.40	0.80	<.01	0.28	0.054	0.001	0.06	0.85	<.01	0.16	<.001	<.001	0.02	2.97
CMC 05-05	25672	44.40	45.20	0.80	<.01	0.28	0.016	0.001	0.05	0.6	<.01	0.21	0.001	<.001	0.18	3.5
CMC 05-05	25673	45.20	46.20	1.00	<.01	0.1	0.043	<.001	0.01	0.46	<.01	0.39	<.001	<.001	0.02	5.3
CMC 05-05	25978	46.20	47.70	1.50	<.01	0.16	0.037	<.001	0.01	0.43	0.01	0.35	<.001	<.001	<.01	4.79
CMC 05-05	25979	47.70	49.00	1.30	<.01	0.26	0.05	<.001	0.02	0.5	0.01	0.39	<.001	<.001	<.01	5.81
CMC 05-05	25674	49.00	50.00	1.00	<.01	0.72	0.06	<.001	0.07	0.65	<.01	0.35	<.001	<.001	<.01	4.35
CMC 05-05	25675	50.00	51.20	1.20	<.01	0.7	0.048	<.001	0.09	0.46	<.01	0.33	<.001	<.001	0.01	6.47
CMC 05-06	25676	4.90	6.50	1.60	<.01	4.83	0.072	0.003	0.49	2.21	<.01	0.19	0.006	<.001	0.01	4.97
CMC 05-06	25677	N/A	N/A	N/A	0.01	0.52	0.008	0.003	0.09	0.23	<.01	0.14	<.001	0.001	0.1	-
CMC 05-06	25678	6.50	8.00	1.50	<.01	6.63	0.077	0.003	0.6	2.49	<.01	0.03	0.021	<.001	0.01	4.29
CMC 05-06	25679	8.00	9.50	1.50	<.01	0.48	0.086	0.003	0.51	1.67	<.01	0.45	0.002	<.001	<.01	6.38
CMC 05-06	25680	9.50	11.00	1.50	<.01	0.21	0.073	0.003	0.31	1.28	<.01	0.54	0.001	<.001	0.01	4.85
CMC 05-06	25681	11.00	12.50	1.50	<.01	0.17	0.066	0.005	0.69	1.82	<.01	0.35	0.001	<.001	<.01	3.85
CMC 05-06	25682	12.50	14.00	1.50	<.01	0.12	0.041	0.005	0.58	1.8	<.01	0.48	<.001	<.001	<.01	4.82
CMC 05-06	25683	14.00	15.50	1.50	<.01	0.12	0.044	0.004	0.42	1.41	<.01	0.44	0.001	<.001	<.01	2.9
CMC 05-06	25684	14.00	15.50	1.50	<.01	0.28	0.035	0.004	0.43	1.46	<.01	0.44	<.001	<.001	<.01	2.32
CMC 05-06	25685	15.50	17.00	1.50	<.01	1.21	0.043	0.004	0.56	2.03	<.01	0.34	0.001	<.001	<.01	4.19
CMC 05-06	25686	17.00	18.50	1.50	<.01	1.36	0.052	0.004	0.76	2.17	<.01	0.4	0.001	<.001	<.01	4.66
CMC 05-06	25687	18.50	20.00	1.50	<.01	0.68	0.048	0.004	0.48	1.67	<.01	0.48	0.002	<.001	0.01	6.96

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-06	25688	20.00	21.50	1.50	0.001	0.01	0.01	1.99	3	0.002	0.001	0.36	3.48	0.01	0.002	0.002	0.001
CMC 05-06	25689	21.50	23.05	1.55	<.001	0.003	0.07	0.68	3	0.003	0.001	0.7	4.94	0.02	0.001	0.001	0.001
CMC 05-06	25690	23.05	24.05	1.00	<.001	0.002	0.12	0.52	7	0.002	0.001	0.96	5.57	0.02	<.001	0.001	<.001
CMC 05-06	25691	24.05	25.05	1.00	<.001	0.003	0.18	0.45	12	0.002	<.001	1.17	5.55	0.01	<.001	0.001	0.001
CMC 05-06	25692	25.05	26.30	1.25	<.001	0.002	0.06	0.7	4	0.001	0.001	1.49	6.66	0.09	0.002	0.004	0.001
CMC 05-06	25693	26.30	27.30	1.00	0.002	0.055	0.06	2.57	66	0.001	0.001	4.63	11.4	0.62	0.005	0.015	0.012
CMC 05-06	25694	27.30	28.30	1.00	0.025	0.029	0.25	1.72	36	0.003	0.001	6.63	16.71	0.27	0.008	0.009	0.003
CMC 05-06	25695	28.30	29.30	1.00	<.001	0.007	0.04	1.52	<2	0.002	<.001	5.47	18.52	0.1	0.003	0.005	0.001
CMC 05-06	25696	29.30	30.30	1.00	<.001	0.003	0.05	1.39	<2	0.002	<.001	7.98	20.49	0.06	0.003	0.003	0.001
CMC 05-06	25697	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.14	<.01	0.004	<.001	<.001
CMC 05-06	25698	30.30	31.30	1.00	0.002	0.013	0.09	2.23	6	0.002	<.001	3.27	12.45	0.33	0.006	0.007	0.003
CMC 05-06	25699	31.30	32.30	1.00	<.001	0.005	0.07	1.79	8	0.002	0.001	6.92	15.89	0.16	0.003	0.005	0.001
CMC 05-06	25700	32.30	33.30	1.00	<.001	0.002	0.16	0.96	6	0.002	<.001	5.95	9.62	0.17	0.004	0.003	0.001
CMC 05-06	25701	33.30	34.10	0.80	<.001	0.002	0.09	1.77	4	0.003	0.001	2.96	6.53	0.06	0.002	0.003	0.001
CMC 05-06	25702	34.10	35.10	1.00	<.001	0.004	<.01	2.08	3	0.001	<.001	10.17	22.52	0.06	0.008	0.006	0.002
CMC 05-06	25703	35.10	36.10	1.00	0.001	0.001	<.01	1.57	<2	0.001	<.001	12.41	25.39	0.02	0.013	0.003	<.001
CMC 05-06	25704	36.10	36.70	0.60	0.015	0.005	<.01	4.24	3	0.003	0.002	15.57	26.94	0.35	0.064	0.01	0.001
CMC 05-06	25705	36.70	38.10	1.40	0.01	0.004	0.03	4.49	<2	0.002	0.001	17.07	26.64	0.13	0.054	0.008	<.001
CMC 05-06	25706	N/A	N/A	N/A	0.074	0.841	0.15	0.09	801	<.001	<.001	0.02	1.45	0.05	0.008	0.001	0.19
CMC 05-07	25707	3.20	5.10	1.90	0.004	0.011	0.14	4.87	57	0.003	0.003	7.63	28.79	0.19	0.026	0.022	0.002
CMC 05-07	25708	5.10	6.85	1.75	0.001	0.015	<.01	2.7	6	0.001	0.001	0.4	2.23	0.01	0.019	0.003	<.001
CMC 05-07	25709	6.85	8.40	1.55	0.001	0.007	0.35	2.85	26	0.002	0.001	3.08	8.29	0.06	0.01	0.008	0.001
CMC 05-07	25710	8.40	9.50	1.10	0.002	0.019	0.11	2.95	70	0.001	<.001	7.99	35.35	0.16	0.016	0.015	0.003
CMC 05-07	25711	9.50	10.60	1.10	0.002	0.017	0.16	2.84	77	0.001	<.001	7.41	31.75	0.12	0.018	0.016	0.002
CMC 05-07	25712	10.60	11.85	1.25	0.001	0.006	0.1	4.17	14	0.001	0.001	1.99	6.5	0.04	0.01	0.008	<.001
CMC 05-07	25713	11.85	13.30	1.45	0.002	0.054	0.29	4.42	68	0.001	0.001	3.8	15.34	0.13	0.01	0.022	0.003
CMC 05-07	25714	11.85	13.30	1.45	0.002	0.05	0.36	4.7	92	0.001	0.001	3.18	13.4	0.18	0.009	0.024	0.006
CMC 05-07	25715	13.30	14.75	1.45	0.002	0.021	0.16	3.65	43	0.002	0.001	2.75	11.28	0.08	0.011	0.012	0.002
CMC 05-07	25716	14.75	17.70	2.95	0.005	0.01	0.2	7.16	116	0.004	0.003	4.58	10.82	0.24	0.016	0.027	0.003
CMC 05-07	25717	17.70	23.15	5.45	0.001	0.025	0.16	2.57	80	0.001	0.001	0.82	9.59	1.76	0.004	0.024	0.013
CMC 05-07	25718	N/A	N/A	N/A	<.001	<.001	<.01	0.02	<2	<.001	<.001	0.02	0.14	<.01	0.004	<.001	0.001
CMC 05-07	25719	23.15	23.70	0.55	0.005	0.059	0.58	7.73	170	0.002	0.002	4.79	12.01	0.88	0.008	0.023	0.008
CMC 05-07	25720	23.70	25.90	2.20	0.008	0.207	0.09	10.77	145	0.002	0.001	5.49	13.95	0.21	0.016	0.022	0.004
CMC 05-07	25721	25.90	26.30	0.40	0.001	0.017	<.01	1.27	6	<.001	<.001	1	3.79	0.04	0.004	0.003	0.001
CMC 05-07	25722	26.30	26.60	0.30	0.002	0.028	0.08	2.13	32	<.001	0.001	2.9	10.32	1.33	0.015	0.01	0.005

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-06	25688	20.00	21.50	1.50	<.01	1.09	0.062	0.002	0.32	1.41	<.01	0.45	0.005	<.001	0.01	7.35
CMC 05-06	25689	21.50	23.05	1.55	<.01	0.33	0.133	0.001	0.22	0.88	<.01	0.54	<.001	<.001	<.01	6.87
CMC 05-06	25690	23.05	24.05	1.00	<.01	0.15	0.043	0.001	0.16	0.78	<.01	0.46	<.001	<.001	0.01	4.52
CMC 05-06	25691	24.05	25.05	1.00	<.01	0.15	0.04	0.001	0.24	0.68	0.03	0.48	<.001	<.001	<.01	3.41
CMC 05-06	25692	25.05	26.30	1.25	<.01	0.17	0.057	0.001	0.16	0.69	<.01	0.47	<.001	<.001	0.01	6.57
CMC 05-06	25693	26.30	27.30	1.00	<.01	0.15	0.012	<.001	0.09	0.39	<.01	0.33	0.002	<.001	0.67	4.65
CMC 05-06	25694	27.30	28.30	1.00	<.01	0.12	0.02	0.002	0.02	0.57	<.01	0.43	0.003	<.001	0.15	4.53
CMC 05-06	25695	28.30	29.30	1.00	<.01	0.13	0.02	<.001	0.01	0.58	<.01	0.44	0.001	<.001	0.01	5.65
CMC 05-06	25696	29.30	30.30	1.00	<.01	0.15	0.015	<.001	0.05	0.5	<.01	0.33	0.001	<.001	0.01	5.2
CMC 05-06	25697	N/A	N/A	N/A	<.01	21.67	0.003	<.001	12.21	0.03	<.01	0.04	<.001	<.001	<.01	5.8
CMC 05-06	25698	30.30	31.30	1.00	<.01	0.23	0.01	0.001	0.06	0.48	0.03	0.34	0.001	<.001	0.03	3.96
CMC 05-06	25699	31.30	32.30	1.00	<.01	0.29	0.011	0.001	0.11	0.63	<.01	0.45	0.002	<.001	0.01	5.69
CMC 05-06	25700	32.30	33.30	1.00	<.01	0.25	0.037	0.001	0.06	0.53	<.01	0.45	<.001	<.001	0.01	5.78
CMC 05-06	25701	33.30	34.10	0.80	<.01	0.14	0.027	0.001	0.03	0.59	<.01	0.54	0.001	<.001	<.01	4.47
CMC 05-06	25702	34.10	35.10	1.00	<.01	0.35	0.159	<.001	0.08	0.2	0.01	0.16	0.001	<.001	0.01	5.31
CMC 05-06	25703	35.10	36.10	1.00	<.01	0.24	0.089	<.001	0.08	0.14	<.01	0.11	0.001	<.001	0.01	5.75
CMC 05-06	25704	36.10	36.70	0.60	<.01	0.25	0.02	<.001	0.05	0.3	0.02	0.18	0.002	<.001	0.02	2.18
CMC 05-06	25705	36.70	38.10	1.40	<.01	0.2	0.017	<.001	0.02	0.13	0.02	0.16	0.002	<.001	0.01	5.5
CMC 05-06	25706	N/A	N/A	N/A	0.01	0.49	0.01	0.003	0.08	0.21	<.01	0.14	<.001	0.001	0.1	-
CMC 05-07	25707	3.20	5.10	1.90	<.01	0.11	0.043	0.002	0.05	0.59	<.01	0.3	0.002	<.001	<.01	7.82
CMC 05-07	25708	5.10	6.85	1.75	<.01	3.86	0.046	0.004	0.63	2.37	0.08	0.2	0.002	<.001	0.01	6.38
CMC 05-07	25709	6.85	8.40	1.55	<.01	0.29	0.058	0.002	0.14	1.09	<.01	0.6	0.002	<.001	<.01	4.85
CMC 05-07	25710	8.40	9.50	1.10	<.01	0.05	0.028	<.001	0.01	0.29	0.01	0.22	0.002	<.001	0.02	6.56
CMC 05-07	25711	9.50	10.60	1.10	<.01	0.03	0.056	<.001	<.01	0.46	<.01	0.39	0.001	<.001	0.01	3.22
CMC 05-07	25712	10.60	11.85	1.25	<.01	2.52	0.048	0.002	0.15	1.83	<.01	0.41	0.003	<.001	<.01	5.76
CMC 05-07	25713	11.85	13.30	1.45	<.01	0.04	0.047	0.001	0.03	0.73	0.01	0.55	0.003	0.001	0.01	3.92
CMC 05-07	25714	11.85	13.30	1.45	<.01	0.09	0.047	0.001	0.03	0.53	<.01	0.48	<.001	<.001	0.02	3.9
CMC 05-07	25715	13.30	14.75	1.45	<.01	0.93	0.057	0.001	0.04	0.91	<.01	0.56	0.003	<.001	0.01	4.15
CMC 05-07	25716	14.75	17.70	2.95	<.01	0.92	0.04	0.001	0.4	0.73	<.01	0.23	<.001	<.001	0.01	3.67
CMC 05-07	25717	17.70	23.15	5.45	<.01	0.19	0.016	<.001	0.02	0.28	<.01	0.25	0.002	<.001	0.28	3.59
CMC 05-07	25718	N/A	N/A	N/A	<.01	23.73	0.01	<.001	12.8	0.04	0.01	<.01	<.001	<.001	0.01	5.28
CMC 05-07	25719	23.15	23.70	0.55	<.01	0.2	0.022	0.003	0.07	0.53	0.01	0.23	0.008	<.001	0.18	2.13
CMC 05-07	25720	23.70	25.90	2.20	0.05	0.25	0.026	0.001	0.09	0.74	<.01	0.2	<.001	<.001	0.08	2.08
CMC 05-07	25721	25.90	26.30	0.40	<.01	0.3	0.045	<.001	0.11	0.41	0.01	0.32	0.002	<.001	0.02	3.41
CMC 05-07	25722	26.30	26.60	0.30	<.01	0.22	0.005	0.001	0.02	0.29	<.01	0.21	0.005	<.001	0.8	1.88

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-07	25723	26.60	28.10	1.50	<.001	0.008	<.01	0.47	2	0.002	0.001	0.48	6.18	0.01	0.004	0.001	0.001
CMC 05-07	25724	28.10	29.60	1.50	<.001	0.005	<.01	0.45	<2	0.002	0.001	0.45	4	<.01	0.013	<.001	0.001
CMC 05-07	25725	29.60	31.55	1.95	<.001	<.001	0.01	0.4	<2	<.001	<.001	0.18	1.35	<.01	0.018	<.001	0.001
CMC 05-07	25726	31.55	32.95	1.40	0.004	0.005	0.04	1.24	6	0.004	0.001	3.9	8.47	0.01	0.042	0.002	<.001
CMC 05-07	25727	32.95	34.60	1.65	<.001	0.003	<.01	0.14	<2	0.001	<.001	0.45	2.35	<.01	0.012	<.001	<.001
CMC 05-07	25728	34.60	36.25	1.65	<.001	0.001	0.01	0.3	<2	<.001	0.001	0.69	3.38	0.01	0.016	<.001	0.001
CMC 05-07	25729	36.25	38.25	2.00	<.001	0.001	<.01	0.05	<2	0.001	0.001	0.28	2.05	<.01	0.015	<.001	<.001
CMC 05-07	25730	38.25	40.25	2.00	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.24	1.93	<.01	0.009	<.001	<.001
CMC 05-07	25731	40.25	42.00	1.75	<.001	<.001	<.01	0.03	<2	0.001	0.001	0.2	1.31	<.01	0.066	<.001	<.001
CMC 05-07	25732	42.00	43.00	1.00	<.001	<.001	<.01	0.13	<2	<.001	<.001	0.99	3.58	<.01	0.119	<.001	0.001
CMC 05-07	25733	N/A	N/A	N/A	0.075	0.845	0.15	0.09	803	<.001	<.001	0.02	1.46	0.05	0.008	0.001	0.191
CMC 05-07	25734	43.00	43.90	0.90	0.002	0.002	<.01	0.99	3	0.002	0.002	1.09	2.3	0.01	0.016	0.001	0.001
CMC 05-07	25735	43.90	45.10	1.20	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.09	0.73	<.01	0.026	<.001	<.001
CMC05-07	25983	N/A	N/A	N/A	<.001	0.003	1.55	0.16	13	0.001	<.001	0.01	5.16	0.04	<.001	0.001	0.001
CMC 05-08	25736	8.50	10.50	2.00	0.002	<.001	<.01	0.05	<2	0.001	<.001	0.33	2.24	<.01	0.006	<.001	0.001
CMC 05-08	25737	N/A	N/A	N/A	0.075	0.851	0.15	0.09	805	<.001	<.001	0.02	1.48	0.05	0.008	0.001	0.194
CMC 05-08	25738	10.50	11.60	1.10	<.001	<.001	<.01	0.06	<2	<.001	<.001	0.35	2.62	<.01	0.006	<.001	0.001
CMC 05-08	25739	11.60	12.70	1.10	<.001	<.001	<.01	0.57	3	<.001	<.001	0.38	1.83	<.01	0.015	0.001	<.001
CMC 05-08	25740	12.70	13.90	1.20	<.001	<.001	<.01	1.11	5	<.001	0.002	0.28	2.68	<.01	0.01	0.004	<.001
CMC 05-08	25741	13.90	15.10	1.20	0.002	0.001	<.01	0.2	<2	<.001	<.001	0.19	1.38	<.01	0.021	0.001	0.001
CMC 05-08	25742	15.10	16.60	1.50	0.001	0.014	<.01	0.1	2	0.003	0.001	0.03	3.38	<.01	0.011	<.001	0.001
CMC 05-08	25743	16.60	18.10	1.50	<.001	0.027	<.01	0.09	<2	0.004	0.002	0.05	3.63	<.01	0.018	<.001	0.001
CMC 05-08	25744	16.60	18.10	1.50	<.001	0.024	<.01	0.09	2	0.004	0.001	0.06	3.56	<.01	0.018	<.001	<.001
CMC 05-08	25745	18.10	19.60	1.50	<.001	0.014	0.01	0.06	4	0.003	0.002	0.14	3.88	0.22	0.019	<.001	0.004
CMC 05-08	25746	19.60	21.10	1.50	0.001	0.008	0.01	0.18	3	0.003	0.001	0.09	3.11	0.01	0.015	<.001	<.001
CMC 05-08	25747	21.10	22.50	1.40	0.001	0.017	0.19	1.86	30	0.002	0.001	2.6	10.56	0.18	0.008	0.007	0.004
CMC 05-08	25748	22.50	23.00	0.50	0.001	0.052	0.28	1.78	67	0.001	0.001	1.84	8.08	0.06	0.006	0.005	0.001
CMC 05-08	25749	23.00	23.25	0.25	0.022	0.297	30.57	5.53	4648	0.001	0.001	10.02	18.82	0.41	0.021	0.022	0.156
CMC 05-08	25750	23.25	24.00	0.75	<.001	0.036	0.2	1.68	76	0.001	0.001	7.43	27.31	0.47	0.013	0.018	0.002
CMC 05-08	25751	N/A	N/A	N/A	0.073	0.89	0.15	0.08	820	<.001	<.001	0.02	1.55	0.05	0.008	0.001	0.206
CMC 05-08	25752	24.00	24.60	0.60	0.002	0.212	1.98	1.37	901	0.001	<.001	1.26	10.2	1.06	0.003	0.016	0.014
CMC 05-08	25753	24.60	25.45	0.85	0.007	0.297	1.56	4.91	520	0.002	0.003	7.78	17.36	0.77	0.016	0.041	0.009
CMC 05-08	25754	25.45	26.50	1.05	0.001	0.017	0.04	1.16	19	<.001	<.001	1.24	6.43	0.03	0.007	0.004	<.001
CMC 05-08	25755	26.50	27.50	1.00	0.005	0.015	0.04	2.3	17	0.001	<.001	4.3	22.69	0.14	0.019	0.01	0.001
CMC 05-08	25756	27.50	28.50	1.00	0.002	0.008	0.04	0.99	13	0.001	<.001	5.51	20.26	0.02	0.019	0.011	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-07	25723	26.60	28.10	1.50	0.04	8.29	0.043	0.002	0.23	1.98	0.01	0.03	0.01	<.001	0.74	7.96
CMC 05-07	25724	28.10	29.60	1.50	<.01	8.17	0.05	0.002	0.29	1.96	<.01	0.02	0.004	<.001	0.13	4.53
CMC 05-07	25725	29.60	31.55	1.95	0.01	7.97	0.061	0.002	0.44	1.78	<.01	0.06	0.005	<.001	0.17	3.52
CMC 05-07	25726	31.55	32.95	1.40	<.01	3.06	0.058	0.002	0.11	1.31	0.02	0.26	0.015	<.001	0.01	5.92
CMC 05-07	25727	32.95	34.60	1.65	<.01	6.92	0.04	0.003	0.11	2.32	<.01	0.03	0.004	<.001	0.01	7.28
CMC 05-07	25728	34.60	36.25	1.65	<.01	6.35	0.036	0.002	0.14	2.29	0.02	0.07	0.002	<.001	<.01	4.89
CMC 05-07	25729	36.25	38.25	2.00	<.01	9.51	0.029	0.002	0.11	1.87	0.02	0.01	0.007	<.001	<.01	11.07
CMC 05-07	25730	38.25	40.25	2.00	<.01	7.46	0.039	0.002	0.15	1.97	<.01	<.01	0.001	<.001	<.01	10.46
CMC 05-07	25731	40.25	42.00	1.75	<.01	14.75	0.052	0.002	0.12	1.31	<.01	0.02	0.001	<.001	0.01	9.38
CMC 05-07	25732	42.00	43.00	1.00	<.01	18.55	0.05	0.001	0.08	0.66	<.01	0.13	<.001	<.001	0.01	2.96
CMC 05-07	25733	N/A	N/A	N/A	<.01	0.53	0.01	0.003	0.08	0.2	0.03	0.12	<.001	0.001	0.11	-
CMC 05-07	25734	43.00	43.90	0.90	<.01	4.26	0.075	0.002	0.32	1.63	<.01	0.05	0.011	<.001	0.02	3.08
CMC 05-07	25735	43.90	45.10	1.20	<.01	10.3	0.066	0.002	0.07	1.11	0.02	0.02	0.001	<.001	<.01	6.87
CMC05-07	25983	N/A	N/A	N/A	<.01	0.11	0.002	0.001	0.05	0.08	<.01	0.06	0.001	<.001	<.01	0.76
CMC 05-08	25736	8.50	10.50	2.00	0.02	8.56	0.059	0.003	0.4	2.43	<.01	<.01	0.001	<.001	0.03	9.31
CMC 05-08	25737	N/A	N/A	N/A	<.01	0.5	0.008	0.003	0.08	0.2	<.01	0.11	<.001	0.001	0.11	-
CMC 05-08	25738	10.50	11.60	1.10	<.01	8.32	0.055	0.003	0.25	2.32	<.01	0.02	0.001	<.001	0.01	6.72
CMC 05-08	25739	11.60	12.70	1.10	<.01	14.95	0.044	0.001	0.26	1.53	<.01	0.06	0.003	<.001	<.01	5.85
CMC 05-08	25740	12.70	13.90	1.20	0.05	11.01	0.048	0.002	0.18	2.07	0.01	<.01	0.021	<.001	0.08	6.68
CMC 05-08	25741	13.90	15.10	1.20	<.01	12.36	0.047	0.002	0.28	1.67	0.02	0.07	0.002	<.001	<.01	7.02
CMC 05-08	25742	15.10	16.60	1.50	<.01	0.96	0.032	0.006	1.28	2.32	0.13	0.72	<.001	<.001	0.02	4.31
CMC 05-08	25743	16.60	18.10	1.50	<.01	2.21	0.043	0.005	0.84	1.82	0.08	0.35	<.001	<.001	0.01	4.75
CMC 05-08	25744	16.60	18.10	1.50	<.01	2.21	0.037	0.004	0.86	1.96	0.08	0.38	<.001	<.001	0.01	5.27
CMC 05-08	25745	18.10	19.60	1.50	<.01	3.75	0.078	0.003	0.89	1.47	0.05	0.3	0.001	<.001	0.01	5.83
CMC 05-08	25746	19.60	21.10	1.50	<.01	2.5	0.035	0.003	0.86	1.71	0.05	0.42	<.001	<.001	<.01	6.01
CMC 05-08	25747	21.10	22.50	1.40	<.01	0.4	0.038	0.001	0.15	0.9	<.01	0.47	<.001	<.001	0.02	5.86
CMC 05-08	25748	22.50	23.00	0.50	<.01	0.09	0.042	0.001	0.01	0.54	<.01	0.42	<.001	<.001	0.02	1.93
CMC 05-08	25749	23.00	23.25	0.25	<.01	0.07	0.002	<.001	<.01	0.1	<.01	0.06	<.001	<.001	0.15	1.78
CMC 05-08	25750	23.25	24.00	0.75	<.01	0.08	0.001	<.001	<.01	0.24	<.01	0.12	<.001	<.001	0.09	4.53
CMC 05-08	25751	N/A	N/A	N/A	0.01	0.52	0.008	0.003	0.1	0.19	0.02	0.13	<.001	<.001	0.11	-
CMC 05-08	25752	24.00	24.60	0.60	<.01	0.07	0.024	0.002	0.05	0.76	0.01	0.09	<.001	<.001	0.41	1.51
CMC 05-08	25753	24.60	25.45	0.85	<.01	0.15	0.017	<.001	0.03	0.61	0.01	0.16	<.001	<.001	0.26	3.38
CMC 05-08	25754	25.45	26.50	1.05	<.01	0.04	0.028	0.001	0.01	0.46	0.01	0.33	<.001	<.001	0.01	3.49
CMC 05-08	25755	26.50	27.50	1.00	<.01	0.08	0.018	<.001	<.01	0.35	<.01	0.21	<.001	<.001	0.01	3.45
CMC 05-08	25756	27.50	28.50	1.00	<.01	0.08	0.014	<.001	0.01	0.42	0.01	0.27	<.001	<.001	0.01	3.42

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-08	25757	28.50	29.15	0.65	0.003	0.009	0.03	1.52	11	0.001	<.001	4.85	20.49	0.04	0.018	0.01	<.001
CMC 05-08	25758	29.15	30.00	0.85	0.003	0.006	0.14	1.48	44	0.002	<.001	2.97	14.49	0.01	0.021	0.004	<.001
CMC 05-08	25759	30.00	30.80	0.80	0.001	0.002	0.01	0.61	13	0.003	0.001	1.66	8.31	0.01	0.013	0.002	<.001
CMC 05-08	25760	30.80	31.70	0.90	0.003	0.002	0.04	0.79	22	0.003	0.001	2.84	11.64	0.02	0.026	0.002	<.001
CMC 05-08	25761	31.70	32.70	1.00	<.001	0.023	0.02	0.37	4	0.004	0.002	0.28	5.48	0.01	0.005	<.001	<.001
CMC 05-08	25762	32.70	33.70	1.00	<.001	0.023	<.01	0.7	<2	0.005	0.002	0.12	5.81	<.01	0.002	<.001	<.001
CMC 05-08	25763	33.70	34.70	1.00	<.001	0.02	<.01	0.45	<2	0.004	0.002	0.13	4.92	<.01	0.003	<.001	<.001
CMC 05-08	25764	34.70	36.00	1.30	0.003	0.01	0.01	0.91	16	0.003	0.001	4.25	18.74	0.02	0.034	0.003	<.001
CMC 05-08	25765	36.00	36.50	0.50	<.001	0.009	<.01	0.1	<2	0.004	0.002	0.07	5.8	<.01	0.004	<.001	<.001
CMC 05-08	25766	36.50	37.50	1.00	0.001	0.029	<.01	0.07	<2	0.005	0.002	0.29	4.72	<.01	0.005	<.001	<.001
CMC 05-08	25767	N/A	N/A	N/A	0.073	0.885	0.14	0.08	802	0.001	<.001	0.01	1.49	0.05	0.008	0.001	0.206
CMC 05-08	25768	37.50	38.50	1.00	0.001	0.029	<.01	0.06	2	0.007	0.002	0.11	8.27	<.01	0.007	<.001	<.001
CMC 05-08	25769	38.50	39.50	1.00	0.001	0.012	<.01	0.03	<2	0.005	0.002	0.18	6.11	<.01	0.008	<.001	<.001
CMC 05-08	25770	39.50	40.50	1.00	0.001	0.004	0.01	0.08	2	0.004	0.002	0.18	5.92	<.01	0.005	<.001	0.001
CMC 05-08	25771	40.50	41.40	0.90	0.001	0.012	<.01	0.03	<2	0.002	0.001	0.41	9.75	0.01	0.021	<.001	<.001
CMC 05-08	25772	41.40	43.40	2.00	0.006	0.003	<.01	0.02	<2	0.003	0.001	0.11	3.14	<.01	0.023	<.001	<.001
CMC 05-08	25773	43.40	45.40	2.00	<.001	0.015	<.01	0.02	<2	0.004	0.001	0.07	2.78	<.01	0.02	<.001	<.001
CMC 05-08	25774	43.40	45.40	2.00	0.001	0.017	<.01	0.01	<2	0.004	0.001	0.07	2.93	<.01	0.02	<.001	<.001
CMC 05-08	25775	45.40	47.40	2.00	<.001	0.011	<.01	<.01	<2	0.004	0.001	0.03	3.19	<.01	0.015	<.001	<.001
CMC 05-08	25776	47.40	49.40	2.00	<.001	0.005	<.01	0.01	<2	0.003	0.001	0.01	2.31	<.01	0.011	<.001	<.001
CMC 05-08	25777	49.40	51.40	2.00	<.001	0.007	<.01	0.01	<2	0.003	0.001	0.02	2.51	<.01	0.013	<.001	<.001
CMC 05-08	25778	51.40	52.70	1.30	0.001	0.004	<.01	0.02	<2	0.002	0.001	0.03	1.3	<.01	0.012	<.001	<.001
CMC 05-09	25779	6.10	6.50	0.40	0.002	0.003	0.11	1.86	24	0.001	<.001	8.61	16.14	0.01	0.013	0.01	<.001
CMC 05-09	25780	6.50	7.50	1.00	0.004	0.007	0.05	2.44	53	0.001	<.001	11.49	40.56	0.06	0.015	0.02	<.001
CMC 05-09	25781	7.50	8.50	1.00	0.003	0.006	0.06	3.36	120	0.001	<.001	9.52	35.61	0.04	0.012	0.018	<.001
CMC 05-09	25782	8.50	9.50	1.00	0.003	0.003	0.02	3.31	18	0.001	<.001	11.84	40.21	0.02	0.014	0.016	<.001
CMC 05-09	25783	9.50	10.60	1.10	0.003	0.002	0.01	3.69	6	0.001	<.001	10.54	38.72	0.06	0.011	0.02	<.001
CMC 05-09	25784	10.60	11.90	1.30	0.003	0.004	0.03	3.98	18	0.001	<.001	7.9	42.51	0.28	0.011	0.017	<.001
CMC 05-09	25785	11.90	13.70	1.80	0.003	0.013	0.11	4.26	93	0.001	<.001	6.51	43.67	0.22	0.011	0.02	0.001
CMC 05-09	25786	13.70	14.60	0.90	0.003	0.007	0.1	4.16	54	0.001	<.001	8.18	38.63	0.1	0.012	0.019	0.004
CMC 05-09	25787	14.60	15.60	1.00	0.004	0.005	0.06	4.14	39	0.001	<.001	9.17	39.58	0.05	0.015	0.02	0.002
CMC 05-09	25788	15.60	17.60	2.00	0.005	0.003	0.03	2.51	92	0.001	<.001	10.91	42.07	0.08	0.018	0.019	<.001
CMC 05-09	25789	17.60	18.50	0.90	0.003	0.013	0.05	2.76	86	0.001	<.001	8.35	41.97	0.12	0.014	0.017	<.001
CMC 05-09	25790	18.50	20.10	1.60	0.004	0.063	0.37	2.04	408	0.003	0.001	7.28	10.59	0.1	0.03	0.01	0.004
CMC 05-09	25791	20.10	21.00	0.90	0.002	0.037	0.08	0.95	250	0.004	0.001	4.15	11.7	0.19	0.031	0.007	0.002

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-08	25757	28.50	29.15	0.65	<.01	0.1	0.021	<.001	<.01	0.39	0.01	0.29	<.001	<.001	0.01	3.19
CMC 05-08	25758	29.15	30.00	0.85	0.02	0.58	0.043	0.001	0.06	0.93	0.01	0.5	<.001	<.001	0.01	5.38
CMC 05-08	25759	30.00	30.80	0.80	0.01	2.57	0.045	0.002	0.23	1.39	0.01	0.43	<.001	<.001	<.01	3.75
CMC 05-08	25760	30.80	31.70	0.90	0.01	1.82	0.033	0.002	0.18	1.27	0.01	0.42	<.001	<.001	0.01	1.87
CMC 05-08	25761	31.70	32.70	1.00	<.01	0.88	0.047	0.002	0.34	1.46	0.01	0.43	<.001	<.001	<.01	3.57
CMC 05-08	25762	32.70	33.70	1.00	<.01	0.38	0.049	0.004	0.8	2.41	0.01	0.48	<.001	<.001	<.01	3.49
CMC 05-08	25763	33.70	34.70	1.00	<.01	0.51	0.05	0.005	1.02	2.63	0.01	0.55	<.001	<.001	<.01	3.78
CMC 05-08	25764	34.70	36.00	1.30	<.01	0.33	0.044	0.001	0.05	0.65	0.01	0.45	0.001	<.001	0.01	2.23
CMC 05-08	25765	36.00	36.50	0.50	<.01	0.79	0.04	0.004	0.72	3.15	0.01	0.66	<.001	<.001	<.01	2.26
CMC 05-08	25766	36.50	37.50	1.00	<.01	2.24	0.03	0.002	0.22	1.03	<.01	0.37	<.001	<.001	0.01	1.55
CMC 05-08	25767	N/A	N/A	N/A	0.01	0.52	0.008	0.003	0.1	0.19	0.02	0.13	<.001	<.001	0.11	-
CMC 05-08	25768	37.50	38.50	1.00	<.01	0.87	0.05	0.011	2.48	6.27	0.03	2.43	<.001	<.001	<.01	1.96
CMC 05-08	25769	38.50	39.50	1.00	<.01	3.62	0.062	0.004	0.7	2.43	0.01	0.46	<.001	<.001	0.01	2.36
CMC 05-08	25770	39.50	40.50	1.00	<.01	1.83	0.036	0.005	0.85	2.62	0.01	0.7	<.001	<.001	<.01	5.72
CMC 05-08	25771	40.50	41.40	0.90	<.01	13.03	0.04	0.001	0.48	1.35	<.01	0.13	0.007	<.001	0.01	4.95
CMC 05-08	25772	41.40	43.40	2.00	<.01	4.45	0.04	0.003	0.75	1.5	0.08	0.32	<.001	<.001	0.01	8.58
CMC 05-08	25773	43.40	45.40	2.00	<.01	3	0.06	0.005	0.72	2.37	0.23	0.26	0.003	<.001	0.01	8.61
CMC 05-08	25774	43.40	45.40	2.00	<.01	2.88	0.058	0.005	0.77	2.51	0.23	0.24	0.004	<.001	<.01	8.92
CMC 05-08	25775	45.40	47.40	2.00	<.01	2.04	0.06	0.006	0.75	2.31	0.2	0.36	<.001	<.001	0.01	9.06
CMC 05-08	25776	47.40	49.40	2.00	<.01	2.04	0.041	0.004	0.45	1.72	0.17	0.32	0.001	<.001	<.01	8.62
CMC 05-08	25777	49.40	51.40	2.00	<.01	1.52	0.042	0.005	0.59	2.08	0.2	0.37	0.001	<.001	0.01	7.85
CMC 05-08	25778	51.40	52.70	1.30	<.01	1.84	0.033	0.003	0.24	1.08	0.11	0.12	<.001	<.001	0.01	5.19
CMC 05-09	25779	6.10	6.50	0.40	<.01	1.31	0.054	<.001	0.33	0.78	0.03	0.45	<.001	<.001	0.01	1.38
CMC 05-09	25780	6.50	7.50	1.00	<.01	0.1	0.037	<.001	<.01	0.21	0.01	0.14	<.001	<.001	0.02	2.11
CMC 05-09	25781	7.50	8.50	1.00	<.01	0.07	0.037	<.001	<.01	0.16	0.01	0.11	<.001	<.001	0.01	2.63
CMC 05-09	25782	8.50	9.50	1.00	<.01	0.07	0.025	<.001	<.01	0.17	0.01	0.1	<.001	<.001	0.01	2.48
CMC 05-09	25783	9.50	10.60	1.10	<.01	0.07	0.037	<.001	<.01	0.23	0.01	0.13	<.001	<.001	0.02	2.07
CMC 05-09	25784	10.60	11.90	1.30	<.01	0.05	0.054	<.001	<.01	0.17	<.01	0.11	<.001	<.001	0.03	6.63
CMC 05-09	25785	11.90	13.70	1.80	<.01	0.04	0.023	0.001	<.01	0.17	<.01	0.1	<.001	<.001	0.02	1.56
CMC 05-09	25786	13.70	14.60	0.90	<.01	0.06	0.03	<.001	<.01	0.19	0.01	0.11	<.001	<.001	0.03	2.51
CMC 05-09	25787	14.60	15.60	1.00	<.01	0.05	0.042	<.001	<.01	0.17	0.01	0.13	<.001	<.001	0.01	4.86
CMC 05-09	25788	15.60	17.60	2.00	<.01	0.09	0.033	<.001	<.01	0.19	0.01	0.14	<.001	<.001	0.02	5.11
CMC 05-09	25789	17.60	18.50	0.90	<.01	0.06	0.056	<.001	<.01	0.2	0.01	0.14	<.001	<.001	0.01	5.29
CMC 05-09	25790	18.50	20.10	1.60	<.01	0.91	0.02	0.001	0.27	1.44	0.01	0.51	<.001	<.001	<.01	3.07
CMC 05-09	25791	20.10	21.00	0.90	<.01	0.1	0.023	0.001	0.03	0.88	0.01	0.53	<.001	<.001	0.02	1.68

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-09	25792	21.00	21.65	0.65	0.001	0.022	0.06	0.53	97	0.002	0.001	1.26	4.54	0.03	0.006	0.002	0.002
CMC 05-09	25793	21.65	22.30	0.65	0.003	0.075	0.17	1.12	342	0.005	0.002	3.96	7.02	0.08	0.018	0.006	0.001
CMC 05-09	25794	22.30	23.10	0.80	0.004	0.027	0.43	1.55	251	0.003	0.001	5.24	16.08	0.23	0.023	0.012	0.005
CMC 05-09	25795	23.10	23.95	0.85	0.004	0.036	0.22	1.81	167	0.001	<.001	4.53	18.62	0.42	0.02	0.01	0.003
CMC 05-09	25796	23.95	24.95	1.00	0.003	0.002	0.01	1.36	15	0.001	<.001	3.57	19.05	0.07	0.02	0.004	0.001
CMC 05-09	25797	N/A	N/A	N/A	0.072	0.859	0.14	0.07	852	<.001	<.001	0.02	1.5	0.05	0.008	0.001	0.206
CMC 05-09	25798	24.95	25.95	1.00	0.004	0.005	0.01	2.2	12	0.001	<.001	3.98	22.53	0.07	0.021	0.01	0.003
CMC 05-09	25799	25.95	26.80	0.85	0.003	0.008	0.01	1.92	52	0.001	<.001	3.02	17.63	0.09	0.018	0.005	0.001
CMC 05-09	25800	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.02	0.15	<.01	0.004	<.001	<.001
CMC 05-09	25801	26.80	27.80	1.00	0.003	0.066	0.21	2.44	128	0.001	<.001	4.16	18.94	0.09	0.02	0.009	0.005
CMC 05-09	25802	27.80	28.70	0.90	0.002	0.088	0.13	1.95	100	0.002	0.001	3.3	11.2	0.14	0.019	0.005	0.002
CMC 05-09	25803	27.80	28.70	0.90	0.002	0.073	0.12	1.78	93	0.002	<.001	2.99	11.11	0.1	0.018	0.005	0.001
CMC 05-09	25804	28.70	29.60	0.90	0.001	0.004	0.03	0.5	7	0.002	0.001	1.02	4.55	0.02	0.01	0.001	0.001
CMC 05-09	25805	29.60	31.10	1.50	0.001	0.008	0.02	0.51	9	0.001	<.001	0.72	5.21	0.02	0.005	0.001	0.001
CMC 05-09	25806	31.10	32.10	1.00	0.001	0.008	0.02	0.5	17	0.001	<.001	1.15	5.85	0.02	0.01	0.001	0.002
CMC 05-09	25807	32.10	33.10	1.00	<.001	0.001	0.02	0.22	3	<.001	<.001	0.59	2.65	0.01	0.006	0.001	0.002
CMC 05-09	25808	33.10	34.20	1.10	0.006	0.002	0.01	0.14	<2	0.001	<.001	0.22	1.45	0.02	0.002	<.001	0.002
CMC 05-09	25809	34.20	35.70	1.50	<.001	0.001	0.03	0.15	3	<.001	<.001	0.41	1.55	<.01	0.004	<.001	0.002
CMC 05-09	25810	35.70	37.20	1.50	<.001	<.001	0.02	0.13	<2	<.001	<.001	0.42	1.47	<.01	0.004	<.001	0.002
CMC 05-09	25811	37.20	38.70	1.50	<.001	0.001	0.01	0.06	<2	<.001	<.001	0.17	1	<.01	0.002	<.001	0.001
CMC 05-09	25812	38.70	40.20	1.50	<.001	0.001	0.02	0.07	<2	0.001	<.001	0.23	1.29	<.01	0.004	<.001	0.001
CMC 05-09	25813	40.20	41.60	1.40	<.001	<.001	0.02	0.13	<2	<.001	<.001	0.81	2.95	<.01	0.007	0.001	0.001
CMC 05-09	25814	41.60	43.60	2.00	<.001	<.001	<.01	0.01	<2	<.001	<.001	0.07	0.94	<.01	0.005	<.001	0.001
CMC 05-10	25901	4.60	6.10	1.50	<.001	0.001	<.01	0.07	<2	0.001	<.001	0.03	0.9	<.01	0.001	<.001	<.001
CMC 05-10	25902	6.10	7.60	1.50	<.001	0.001	<.01	0.05	<2	<.001	<.001	0.02	0.92	<.01	0.001	<.001	<.001
CMC 05-10	25903	7.60	9.10	1.50	<.001	0.001	<.01	0.03	<2	<.001	<.001	0.03	0.81	<.01	0.001	<.001	<.001
CMC 05-10	25904	9.10	10.60	1.50	<.001	0.001	<.01	0.06	<2	<.001	<.001	0.03	0.93	<.01	0.001	<.001	<.001
CMC 05-10	25905	10.60	11.60	1.00	<.001	0.006	0.02	0.15	14	<.001	<.001	0.16	1.24	0.01	0.001	<.001	0.002
CMC 05-10	25906	11.60	12.20	0.60	<.001	0.006	0.07	0.24	25	<.001	<.001	0.72	2.6	0.01	0.002	0.001	0.002
CMC 05-10	25907	12.20	13.20	1.00	<.001	0.024	0.17	0.15	165	<.001	<.001	0.29	1.62	0.04	0.001	0.001	0.005
CMC 05-10	25908	13.20	14.20	1.00	<.001	0.014	0.07	0.17	31	<.001	<.001	0.56	1.93	0.01	0.001	0.001	0.002
CMC 05-10	25909	14.20	15.20	1.00	<.001	0.004	0.01	0.68	9	<.001	<.001	0.09	1.05	0.01	0.001	0.001	0.001
CMC 05-10	25910	N/A	N/A	N/A	<.001	0.001	<.01	<.01	<2	<.001	<.001	0.01	0.12	<.01	0.005	<.001	0.001
CMC 05-10	25911	15.20	16.70	1.50	<.001	0.002	<.01	0.18	<2	<.001	<.001	0.03	1.07	<.01	0.002	<.001	0.001
CMC 05-10	25912	16.70	18.20	1.50	<.001	0.004	<.01	0.08	<2	<.001	<.001	0.03	0.88	<.01	0.002	<.001	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-09	25792	21.00	21.65	0.65	<.01	0.07	0.015	0.001	0.02	0.55	<.01	0.4	<.001	<.001	0.01	2.37
CMC 05-09	25793	21.65	22.30	0.65	<.01	0.09	0.026	0.001	0.04	0.97	0.01	0.63	<.001	<.001	0.01	2.26
CMC 05-09	25794	22.30	23.10	0.80	<.01	0.11	0.019	0.001	0.02	0.87	0.01	0.57	<.001	<.001	0.03	2.33
CMC 05-09	25795	23.10	23.95	0.85	<.01	0.11	0.01	<.001	<.01	0.38	<.01	0.26	<.001	<.001	0.04	2.11
CMC 05-09	25796	23.95	24.95	1.00	<.01	0.11	0.022	0.001	<.01	0.41	<.01	0.32	<.001	<.001	0.01	3.71
CMC 05-09	25797	N/A	N/A	N/A	0.01	0.5	0.008	0.003	0.09	0.2	0.02	0.14	<.001	0.001	0.11	-
CMC 05-09	25798	24.95	25.95	1.00	<.01	0.09	0.019	<.001	<.01	0.36	<.01	0.24	<.001	<.001	0.04	2.96
CMC 05-09	25799	25.95	26.80	0.85	<.01	0.1	0.024	0.001	<.01	0.45	<.01	0.3	<.001	<.001	0.02	3.22
CMC 05-09	25800	N/A	N/A	N/A	<.01	19.47	0.001	<.001	11.97	0.01	<.01	0.01	<.001	<.001	<.01	5.73
CMC 05-09	25801	26.80	27.80	1.00	<.01	0.2	0.019	<.001	0.07	0.42	<.01	0.18	<.001	<.001	0.02	3.27
CMC 05-09	25802	27.80	28.70	0.90	<.01	0.16	0.033	0.001	0.02	0.62	<.01	0.31	<.001	<.001	0.04	3.85
CMC 05-09	25803	27.80	28.70	0.90	<.01	0.15	0.031	0.001	0.02	0.65	<.01	0.33	0.001	<.001	0.04	3.91
CMC 05-09	25804	28.70	29.60	0.90	<.01	0.14	0.044	0.001	0.05	1.09	0.01	0.61	<.001	<.001	0.01	2.91
CMC 05-09	25805	29.60	31.10	1.50	<.01	0.12	0.05	0.001	0.02	0.94	<.01	0.61	<.001	<.001	0.01	5.22
CMC 05-09	25806	31.10	32.10	1.00	<.01	0.19	0.052	0.001	0.03	0.96	<.01	0.57	0.001	<.001	0.01	3.31
CMC 05-09	25807	32.10	33.10	1.00	<.01	0.16	0.062	<.001	0.02	0.65	<.01	0.46	<.001	<.001	<.01	2.33
CMC 05-09	25808	33.10	34.20	1.10	<.01	0.14	0.056	<.001	0.02	0.52	<.01	0.43	0.002	<.001	0.01	2.61
CMC 05-09	25809	34.20	35.70	1.50	<.01	0.14	0.053	<.001	0.01	0.6	<.01	0.42	0.001	<.001	<.01	4.83
CMC 05-09	25810	35.70	37.20	1.50	<.01	0.14	0.05	<.001	0.02	0.57	<.01	0.38	<.001	<.001	<.01	5.17
CMC 05-09	25811	37.20	38.70	1.50	<.01	0.6	0.05	<.001	0.03	0.6	0.01	0.35	0.001	<.001	<.01	6.89
CMC 05-09	25812	38.70	40.20	1.50	<.01	0.58	0.047	0.001	0.04	0.52	0.01	0.34	0.001	<.001	<.01	6.19
CMC 05-09	25813	40.20	41.60	1.40	<.01	0.22	0.054	<.001	0.02	0.56	0.01	0.42	0.001	<.001	<.01	4.81
CMC 05-09	25814	41.60	43.60	2.00	<.01	1.13	0.042	0.001	0.13	0.66	0.02	0.28	0.001	<.001	<.01	8.03
CMC 05-10	25901	4.60	6.10	1.50	<.01	0.2	0.051	0.001	0.14	0.52	0.03	0.22	<.001	<.001	<.01	6.39
CMC 05-10	25902	6.10	7.60	1.50	<.01	0.17	0.051	<.001	0.09	0.54	0.04	0.24	<.001	<.001	<.01	5.03
CMC 05-10	25903	7.60	9.10	1.50	<.01	0.18	0.046	<.001	0.11	0.55	0.03	0.19	<.001	<.001	<.01	4.55
CMC 05-10	25904	9.10	10.60	1.50	<.01	0.16	0.049	<.001	0.07	0.53	0.03	0.24	<.001	<.001	<.01	4.19
CMC 05-10	25905	10.60	11.60	1.00	<.01	0.15	0.052	0.001	0.07	0.62	0.01	0.27	<.001	<.001	<.01	2.83
CMC 05-10	25906	11.60	12.20	0.60	<.01	0.09	0.058	<.001	0.03	0.34	<.01	0.31	<.001	<.001	<.01	2.11
CMC 05-10	25907	12.20	13.20	1.00	<.01	0.06	0.05	<.001	0.02	0.36	<.01	0.34	<.001	<.001	0.02	3.49
CMC 05-10	25908	13.20	14.20	1.00	<.01	0.1	0.059	<.001	0.03	0.39	<.01	0.38	<.001	<.001	<.01	4.51
CMC 05-10	25909	14.20	15.20	1.00	<.01	0.14	0.052	0.001	0.06	0.56	0.01	0.26	<.001	<.001	<.01	4.27
CMC 05-10	25910	N/A	N/A	N/A	<.01	19.4	0.001	<.001	11.08	0.02	<.01	0.01	0.001	<.001	<.01	4.26
CMC 05-10	25911	15.20	16.70	1.50	<.01	0.42	0.054	<.001	0.13	0.73	0.01	0.24	<.001	<.001	<.01	6.21
CMC 05-10	25912	16.70	18.20	1.50	<.01	0.32	0.045	<.001	0.11	0.57	0.02	0.2	<.001	<.001	<.01	5.73

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-10	25913	N/A	N/A	N/A	0.076	0.887	0.14	0.08	838	0.001	<.001	0.01	1.48	0.05	0.008	0.001	0.206
CMC 05-10	25914	18.20	19.70	1.50	0.001	0.013	<.01	0.06	3	<.001	<.001	0.02	0.9	<.01	0.002	<.001	0.002
CMC 05-10	25915	19.70	21.50	1.80	<.001	0.011	0.03	0.35	10	<.001	<.001	0.57	1.93	0.01	0.002	0.001	0.001
CMC 05-10	25916	21.50	23.00	1.50	<.001	0.012	0.01	0.12	2	<.001	<.001	0.07	1.01	<.01	0.001	<.001	0.001
CMC 05-10	25917	23.00	24.30	1.30	0.001	0.014	0.04	0.34	11	<.001	<.001	0.3	1.53	0.01	0.001	0.001	0.003
CMC 05-10	25918	24.30	25.30	1.00	<.001	0.006	0.03	0.4	9	<.001	<.001	0.31	1.27	<.01	0.001	0.001	0.001
CMC 05-10	25919	25.30	27.30	2.00	<.001	0.005	0.03	0.26	6	<.001	<.001	0.19	0.97	<.01	0.002	0.001	<.001
CMC 05-10	25920	27.30	28.30	1.00	0.001	0.004	0.01	0.09	<2	<.001	<.001	0.63	2.7	0.01	0.001	0.001	0.002
CMC 05-10	25921	27.30	28.30	1.00	0.001	0.003	0.01	0.08	2	<.001	<.001	0.62	2.71	0.01	0.001	0.001	<.001
CMC 05-10	25957	28.30	29.80	1.50	0.002	0.012	0.04	0.11	18	<.001	<.001	0.14	1.9	0.01	0.002	<.001	0.002
CMC 05-10	25922	29.80	30.65	0.85	<.001	0.006	0.01	0.31	<2	<.001	<.001	0.14	0.77	<.01	0.003	0.001	0.001
CMC 05-10	25923	30.65	32.65	2.00	<.001	0.006	0.04	0.27	5	<.001	<.001	0.39	1.46	<.01	0.002	0.001	0.001
CMC 05-10	25924	32.65	34.65	2.00	0.001	0.001	0.01	0.14	<2	<.001	<.001	0.19	1.17	<.01	0.003	<.001	<.001
CMC 05-10	25980	34.65	36.15	1.50	<.001	<.001	0.01	0.09	<2	<.001	<.001	0.09	0.95	<.01	0.003	<.001	<.001
CMC05-10	25984	34.65	36.15	1.50	0.001	0.006	0.01	0.04	<2	0.002	<.001	1.98	10.51	<.01	0.075	<.001	<.001
CMC05-10	25981	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.09	<.01	0.004	<.001	0.001
CMC05-10	25982	36.15	37.20	1.05	<.001	0.001	<.01	0.05	<2	<.001	<.001	0.02	1.26	<.01	0.002	<.001	<.001
CMC 05-10	25925	37.20	38.70	1.50	0.002	0.001	0.02	0.07	<2	<.001	<.001	0.04	0.81	<.01	0.003	<.001	0.001
CMC 05-10	25926	40.60	42.10	1.50	<.001	0.001	<.01	0.05	<2	<.001	<.001	0.04	1.07	<.01	0.003	<.001	<.001
CMC 05-10	25927	42.10	43.90	1.80	<.001	0.001	<.01	0.05	<2	<.001	<.001	0.04	0.93	<.01	0.003	<.001	0.001
CMC 05-10	25928	43.90	45.10	1.20	<.001	0.002	<.01	0.03	<2	<.001	<.001	0.04	0.67	<.01	0.002	<.001	0.001
CMC 05-11	25929	1.52	3.50	1.98	<.001	0.001	<.01	0.02	<2	<.001	<.001	0.02	0.96	<.01	0.001	<.001	0.002
CMC 05-11	25930	3.50	5.10	1.60	<.001	0.004	<.01	0.05	<2	<.001	<.001	0.06	0.9	<.01	0.001	<.001	<.001
CMC 05-11	25931	5.10	6.20	1.10	0.001	0.005	0.08	0.2	22	<.001	<.001	0.86	2.84	0.01	0.003	0.001	0.001
CMC 05-11	25932	6.20	7.70	1.50	<.001	0.002	0.02	0.18	6	<.001	<.001	0.14	0.92	<.01	0.001	<.001	<.001
CMC 05-11	25933	7.70	8.80	1.10	<.001	0.001	<.01	0.21	2	<.001	<.001	0.06	1.12	<.01	0.001	<.001	<.001
CMC 05-11	25934	8.80	11.00	2.20	<.001	<.001	0.02	0.15	<2	<.001	<.001	0.51	1.73	<.01	0.002	<.001	0.001
CMC 05-11	25935	11.00	12.20	1.20	0.001	0.009	0.01	0.37	22	<.001	<.001	0.38	1.85	<.01	0.001	0.001	0.003
CMC 05-11	25936	12.20	14.20	2.00	<.001	0.002	0.01	0.1	<2	<.001	<.001	0.11	0.92	<.01	0.003	<.001	0.001
CMC 05-11	25937	14.20	16.20	2.00	0.001	0.002	0.02	0.15	6	<.001	<.001	0.32	1.19	<.01	0.003	<.001	0.001
CMC 05-11	25938	16.20	17.70	1.50	<.001	0.003	0.01	0.12	7	<.001	<.001	0.08	0.85	<.01	0.003	<.001	0.001
CMC 05-11	25939	17.70	19.20	1.50	<.001	0.002	0.01	0.2	<2	<.001	<.001	0.07	0.86	0.01	0.001	<.001	0.001
CMC 05-11	25940	19.20	20.70	1.50	<.001	0.001	0.04	0.44	<2	<.001	<.001	0.35	1.12	<.01	0.002	0.001	0.001
CMC 05-11	25941	19.20	20.70	1.50	<.001	0.001	0.04	0.38	2	<.001	<.001	0.36	1.25	0.01	0.002	0.001	<.001
CMC 05-11	25942	N/A	N/A	N/A	0.075	0.899	0.14	0.09	825	0.001	<.001	0.01	1.44	0.05	0.008	0.001	0.2

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-10	25913	N/A	N/A	N/A	0.01	0.51	0.009	0.003	0.09	0.19	0.02	0.13	<.001	0.001	0.13	-
CMC 05-10	25914	18.20	19.70	1.50	<.01	0.66	0.046	<.001	0.25	0.62	0.03	0.24	0.001	<.001	<.01	4.52
CMC 05-10	25915	19.70	21.50	1.80	<.01	0.21	0.057	<.001	0.08	0.59	0.01	0.33	<.001	<.001	<.01	5.63
CMC 05-10	25916	21.50	23.00	1.50	<.01	0.2	0.048	0.001	0.11	0.61	0.02	0.23	<.001	<.001	<.01	2.85
CMC 05-10	25917	23.00	24.30	1.30	<.01	0.11	0.053	0.001	0.03	0.34	<.01	0.3	0.001	<.001	<.01	2.63
CMC 05-10	25918	24.30	25.30	1.00	<.01	0.17	0.057	0.001	0.03	0.38	<.01	0.37	<.001	<.001	<.01	2.41
CMC 05-10	25919	25.30	27.30	2.00	<.01	0.22	0.056	0.001	0.04	0.36	<.01	0.34	<.001	<.001	<.01	7.25
CMC 05-10	25920	27.30	28.30	1.00	<.01	0.1	0.044	0.001	0.09	0.33	<.01	0.35	0.001	<.001	<.01	3.91
CMC 05-10	25921	27.30	28.30	1.00	<.01	0.1	0.041	0.001	0.09	0.36	<.01	0.36	<.001	<.001	<.01	3.85
CMC 05-10	25957	28.30	29.80	1.50	<.01	0.08	0.057	0.001	0.03	0.4	0.01	0.37	0.001	<.001	<.01	5.29
CMC 05-10	25922	29.80	30.65	0.85	<.01	0.33	0.057	<.001	0.05	0.4	<.01	0.33	<.001	<.001	<.01	3.37
CMC 05-10	25923	30.65	32.65	2.00	<.01	0.22	0.057	0.001	0.05	0.38	<.01	0.37	<.001	<.001	<.01	7.58
CMC 05-10	25924	32.65	34.65	2.00	<.01	0.49	0.062	<.001	0.07	0.46	<.01	0.37	<.001	<.001	<.01	6.73
CMC 05-10	25980	34.65	36.15	1.50	<.01	0.67	0.059	0.001	0.07	0.45	0.01	0.34	<.001	<.001	<.01	4.61
CMC05-10	25984	34.65	36.15	1.50	<.01	11.2	0.035	0.003	2.76	3.75	<.01	0.11	<.001	<.001	0.01	0.68
CMC05-10	25981	N/A	N/A	N/A	<.01	19.89	0.001	<.001	12.04	0.02	<.01	0.01	<.001	<.001	0.03	5.03
CMC05-10	25982	36.15	37.20	1.05	<.01	0.39	0.057	<.001	0.15	0.74	0.01	0.28	<.001	<.001	<.01	4.38
CMC 05-10	25925	37.20	38.70	1.50	<.01	0.48	0.062	<.001	0.05	0.48	<.01	0.29	0.001	<.001	<.01	6.18
CMC 05-10	25926	40.60	42.10	1.50	<.01	0.6	0.059	0.001	0.18	1.01	0.01	0.24	0.001	<.001	<.01	3.85
CMC 05-10	25927	42.10	43.90	1.80	<.01	0.59	0.053	<.001	0.12	0.66	<.01	0.29	0.001	<.001	<.01	4.22
CMC 05-10	25928	43.90	45.10	1.20	<.01	0.51	0.049	<.001	0.1	0.42	<.01	0.25	<.001	<.001	<.01	3.51
CMC 05-11	25929	1.52	3.50	1.98	<.01	0.12	0.037	<.001	0.1	0.56	0.04	0.21	0.001	<.001	<.01	2.37
CMC 05-11	25930	3.50	5.10	1.60	<.01	0.15	0.047	<.001	0.06	0.58	0.02	0.24	0.001	<.001	<.01	1.52
CMC 05-11	25931	5.10	6.20	1.10	<.01	0.1	0.045	<.001	0.02	0.39	<.01	0.38	<.001	<.001	<.01	3.85
CMC 05-11	25932	6.20	7.70	1.50	<.01	0.09	0.027	0.001	0.03	0.39	0.01	0.31	<.001	0.001	<.01	4.55
CMC 05-11	25933	7.70	8.80	1.10	<.01	0.12	0.031	<.001	0.09	0.69	0.02	0.25	<.001	<.001	<.01	4.29
CMC 05-11	25934	8.80	11.00	2.20	<.01	0.44	0.053	<.001	0.06	0.41	0.01	0.36	<.001	<.001	<.01	10.27
CMC 05-11	25935	11.00	12.20	1.20	<.01	0.16	0.048	<.001	0.04	0.4	0.01	0.37	<.001	<.001	0.01	5.48
CMC 05-11	25936	12.20	14.20	2.00	<.01	0.61	0.055	<.001	0.04	0.37	0.01	0.36	<.001	<.001	<.01	8.85
CMC 05-11	25937	14.20	16.20	2.00	<.01	0.39	0.053	<.001	0.07	0.38	<.01	0.36	<.001	<.001	<.01	7.22
CMC 05-11	25938	16.20	17.70	1.50	<.01	0.58	0.051	<.001	0.06	0.37	<.01	0.36	<.001	<.001	<.01	5.96
CMC 05-11	25939	17.70	19.20	1.50	<.01	0.13	0.047	0.001	0.02	0.39	<.01	0.36	<.001	<.001	<.01	5.85
CMC 05-11	25940	19.20	20.70	1.50	<.01	0.35	0.055	0.001	0.07	0.37	<.01	0.37	<.001	<.001	<.01	5.35
CMC 05-11	25941	19.20	20.70	1.50	<.01	0.33	0.055	0.001	0.06	0.37	<.01	0.36	<.001	<.001	<.01	6.37
CMC 05-11	25942	N/A	N/A	N/A	<.01	0.51	0.009	0.003	0.09	0.2	0.02	0.13	0.001	0.001	0.1	-

CMC METALS LTD

2005 ASSAY LOG
Holes CMC05-01 to CMC05-14

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-11	25943	20.70	21.50	0.80	0.001	0.007	0.04	0.13	16	<.001	<.001	0.51	1.97	0.01	0.001	0.001	0.003
CMC 05-11	25944	21.50	22.30	0.80	<.001	0.005	0.02	3.17	<2	0.002	0.001	0.26	4.94	0.01	0.007	0.003	0.001
CMC 05-11	25945	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.11	<.01	0.005	<.001	<.001
CMC 05-11	25946	22.30	23.05	0.75	<.001	0.001	0.01	0.06	<2	<.001	<.001	0.15	0.92	<.01	0.001	<.001	0.001
CMC 05-11	25947	23.05	24.70	1.65	0.001	0.002	0.02	0.39	<2	0.001	<.001	0.17	0.86	<.01	0.002	<.001	0.001
CMC 05-11	25948	24.70	26.70	2.00	0.001	<.001	0.01	0.39	<2	<.001	<.001	0.14	0.88	<.01	0.003	<.001	<.001
CMC 05-11	25949	26.70	27.30	0.60	0.001	0.001	0.07	0.39	<2	<.001	<.001	0.62	1.67	<.01	0.001	0.001	0.001
CMC 05-11	25950	27.30	27.75	0.45	0.001	0.001	0.03	0.23	<2	<.001	<.001	0.77	2.35	<.01	0.001	0.001	<.001
CMC 05-11	25951	27.75	28.00	0.25	0.001	0.249	0.03	6.3	1474	<.001	<.001	1.12	3.55	0.07	0.001	0.015	0.201
CMC 05-11	25952	N/A	N/A	N/A	<.001	0.001	<.01	0.02	5	<.001	<.001	0.02	0.12	<.01	0.005	<.001	0.001
CMC 05-11	25953	28.00	28.40	0.40	<.001	0.001	0.02	0.2	4	<.001	<.001	0.88	2.7	<.01	0.001	<.001	0.001
CMC 05-11	25954	28.40	29.90	1.50	<.001	<.001	0.07	0.19	<2	<.001	<.001	0.44	1.37	<.01	0.002	<.001	0.001
CMC 05-11	25955	29.90	31.90	2.00	<.001	0.001	0.01	0.33	<2	<.001	<.001	0.06	0.92	<.01	0.003	<.001	0.001
CMC 05-11	25956	31.90	33.90	2.00	<.001	0.005	0.01	0.17	<2	<.001	<.001	0.04	1.02	<.01	0.004	<.001	0.001
CMC 05-12	25815	10.60	12.60	2.00	0.001	0.007	0.22	0.35	42	<.001	<.001	0.57	2.34	0.02	<.001	0.002	0.003
CMC 05-12	25816	12.60	13.45	0.85	<.001	0.007	0.06	1.1	33	<.001	<.001	0.52	2.17	0.02	<.001	0.003	0.002
CMC 05-12	25817	13.45	13.95	0.50	0.001	0.012	0.15	2.78	21	<.001	<.001	0.18	1.16	<.01	<.001	0.009	0.002
CMC 05-12	25818	13.95	14.45	0.50	<.001	0.003	0.04	0.76	4	<.001	<.001	0.06	0.8	<.01	<.001	0.002	0.001
CMC 05-12	25819	14.45	14.85	0.40	0.001	0.019	0.09	4.97	76	<.001	<.001	0.21	1.33	0.01	<.001	0.017	0.005
CMC 05-12	25820	14.85	15.45	0.60	0.003	0.578	0.29	60.49	2172	<.001	0.002	1.04	4.76	0.12	<.001	0.126	0.217
CMC 05-12	25821	15.45	15.90	0.45	0.001	0.21	0.29	26.49	2566	<.001	0.001	0.65	3.4	0.54	<.001	0.064	0.023
CMC 05-12	25822	15.90	16.20	0.30	<.001	0.005	0.02	0.31	29	<.001	<.001	0.01	0.77	0.04	0.001	0.001	0.003
CMC 05-12	25823	16.20	17.70	1.50	<.001	0.001	0.06	0.42	4	<.001	<.001	0.77	2.15	<.01	0.001	0.001	0.003
CMC 05-12	25824	17.70	19.05	1.35	<.001	0.002	0.01	0.24	6	<.001	<.001	0.22	1.29	<.01	0.003	<.001	0.001
CMC 05-12	25825	19.05	19.60	0.55	<.001	0.002	<.01	1.21	<2	0.005	0.003	0.56	4.69	<.01	0.009	0.001	0.001
CMC 05-12	25826	19.60	21.10	1.50	<.001	0.033	0.04	0.73	29	<.001	<.001	0.35	1.29	<.01	0.001	0.002	0.004
CMC 05-12	25827	N/A	N/A	N/A	0.073	0.898	0.14	0.08	861	<.001	<.001	0.01	1.44	0.05	0.008	0.001	0.206
CMC 05-12	25828	21.10	23.10	2.00	0.001	0.005	<.01	0.79	4	<.001	<.001	0.09	0.8	<.01	0.001	<.001	0.001
CMC 05-12	25829	23.10	25.10	2.00	<.001	0.003	<.01	0.35	<2	<.001	<.001	0.07	0.8	<.01	0.002	<.001	<.001
CMC 05-12	25830	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.09	<.01	0.004	<.001	<.001
CMC 05-12	25831	25.10	27.10	2.00	<.001	0.002	0.01	0.18	<2	<.001	<.001	0.07	0.87	<.01	0.003	<.001	<.001
CMC 05-12	25832	49.10	51.10	2.00	<.001	0.006	0.03	0.09	7	<.001	<.001	0.29	1.43	<.01	0.004	<.001	<.001
CMC 05-12	25833	49.10	51.10	2.00	<.001	0.006	0.03	0.09	6	<.001	<.001	0.32	1.45	<.01	0.005	<.001	<.001
CMC 05-12	25834	51.10	53.10	2.00	<.001	0.003	<.01	<.01	<2	<.001	<.001	0.07	0.97	<.01	0.01	<.001	<.001
CMC 05-12	25835	53.10	55.10	2.00	<.001	0.001	0.01	0.01	<2	<.001	<.001	0.08	1	<.01	0.005	<.001	<.001

CMC METALS LTD

2005 ASSAY LOG
Holes CMC05-01 to CMC05-14

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-11	25943	20.70	21.50	0.80	<.01	0.14	0.057	<.001	0.06	0.4	<.01	0.4	<.001	<.001	<.01	3.19
CMC 05-11	25944	21.50	22.30	0.80	<.01	1.26	0.193	0.004	0.93	4.09	0.01	0.19	<.001	<.001	<.01	0.71
CMC 05-11	25945	N/A	N/A	N/A	<.01	19.2	0.003	<.001	11.8	0.03	<.01	0.01	0.001	<.001	<.01	6.11
CMC 05-11	25946	22.30	23.05	0.75	<.01	0.13	0.036	<.001	0.06	0.3	<.01	0.31	<.001	<.001	0.01	3.07
CMC 05-11	25947	23.05	24.70	1.65	<.01	0.23	0.053	0.001	0.07	0.38	<.01	0.38	0.001	<.001	<.01	7.22
CMC 05-11	25948	24.70	26.70	2.00	<.01	0.44	0.056	0.001	0.08	0.38	<.01	0.37	0.001	<.001	<.01	7.62
CMC 05-11	25949	26.70	27.30	0.60	<.01	0.25	0.059	<.001	0.08	0.39	<.01	0.36	<.001	<.001	<.01	2.65
CMC 05-11	25950	27.30	27.75	0.45	<.01	0.17	0.057	<.001	0.08	0.41	<.01	0.38	<.001	<.001	<.01	1.85
CMC 05-11	25951	27.75	28.00	0.25	<.01	0.09	0.028	<.001	0.07	0.28	<.01	0.29	<.001	<.001	0.14	1.27
CMC 05-11	25952	N/A	N/A	N/A	<.01	20.53	0.002	<.001	12.04	0.02	<.01	0.01	<.001	<.001	<.01	3.75
CMC 05-11	25953	28.00	28.40	0.40	<.01	0.26	0.06	<.001	0.15	0.41	<.01	0.38	<.001	<.001	<.01	2
CMC 05-11	25954	28.40	29.90	1.50	<.01	0.35	0.061	<.001	0.11	0.4	<.01	0.4	0.001	<.001	0.01	5.51
CMC 05-11	25955	29.90	31.90	2.00	<.01	0.56	0.052	0.001	0.1	0.52	0.02	0.33	<.001	<.001	<.01	8.08
CMC 05-11	25956	31.90	33.90	2.00	<.01	0.53	0.049	0.001	0.13	0.51	0.03	0.3	<.001	<.001	<.01	7.26
CMC 05-12	25815	10.60	12.60	2.00	<.01	0.13	0.05	<.001	0.04	0.29	<.01	0.28	<.001	<.001	0.16	6.44
CMC 05-12	25816	12.60	13.45	0.85	<.01	0.09	0.031	<.001	0.05	0.32	<.01	0.3	<.001	<.001	0.02	3.59
CMC 05-12	25817	13.45	13.95	0.50	<.01	0.02	0.014	<.001	0.01	0.21	<.01	0.21	<.001	<.001	0.03	1.81
CMC 05-12	25818	13.95	14.45	0.50	<.01	0.02	0.012	<.001	0.01	0.21	<.01	0.23	<.001	<.001	0.01	1.73
CMC 05-12	25819	14.45	14.85	0.40	<.01	0.03	0.015	<.001	0.03	0.22	<.01	0.26	<.001	0.001	0.04	1.48
CMC 05-12	25820	14.85	15.45	0.60	<.01	0.01	<.001	<.001	0.01	0.05	<.01	0.05	<.001	0.003	0.2	3.45
CMC 05-12	25821	15.45	15.90	0.45	<.01	0.02	0.007	<.001	0.02	0.12	<.01	0.14	<.001	0.001	0.32	2.05
CMC 05-12	25822	15.90	16.20	0.30	<.01	0.04	0.04	<.001	0.01	0.31	<.01	0.44	<.001	<.001	0.02	1.78
CMC 05-12	25823	16.20	17.70	1.50	<.01	0.15	0.057	<.001	0.06	0.37	<.01	0.4	<.001	<.001	<.01	2.41
CMC 05-12	25824	17.70	19.05	1.35	<.01	0.72	0.046	<.001	0.13	0.5	0.02	0.32	<.001	<.001	<.01	5.51
CMC 05-12	25825	19.05	19.60	0.55	<.01	2.49	0.276	0.005	0.81	2.42	0.01	0.15	<.001	<.001	3.31	1.56
CMC 05-12	25826	19.60	21.10	1.50	<.01	0.16	0.051	<.001	0.06	0.36	<.01	0.35	<.001	<.001	<.01	2.67
CMC 05-12	25827	N/A	N/A	N/A	0.01	0.51	0.009	0.003	0.09	0.2	0.02	0.14	<.001	0.001	0.15	-
CMC 05-12	25828	21.10	23.10	2.00	<.01	0.19	0.048	<.001	0.07	0.53	<.01	0.23	<.001	<.001	<.01	3.81
CMC 05-12	25829	23.10	25.10	2.00	<.01	0.36	0.046	<.001	0.08	0.48	<.01	0.27	<.001	<.001	<.01	7.13
CMC 05-12	25830	N/A	N/A	N/A	<.01	20.27	0.003	<.001	11.8	0.02	<.01	0.01	<.001	<.001	<.01	5.03
CMC 05-12	25831	25.10	27.10	2.00	<.01	0.5	0.049	<.001	0.11	0.39	<.01	0.27	<.001	<.001	<.01	6.62
CMC 05-12	25832	49.10	51.10	2.00	<.01	1.25	0.056	<.001	0.15	0.62	<.01	0.37	<.001	<.001	<.01	7.56
CMC 05-12	25833	49.10	51.10	2.00	<.01	1.45	0.056	<.001	0.13	0.38	<.01	0.27	<.001	<.001	<.01	7.71
CMC 05-12	25834	51.10	53.10	2.00	<.01	2.12	0.053	<.001	0.09	0.46	<.01	0.25	<.001	<.001	<.01	7.49
CMC 05-12	25835	53.10	55.10	2.00	<.01	1.53	0.057	<.001	0.13	0.46	<.01	0.32	0.001	<.001	<.01	7.05

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-12	25836	55.10	56.20	1.10	<.001	0.001	<.01	0.01	<2	<.001	<.001	0.07	1.08	<.01	0.004	<.001	0.001
CMC 05-12	25837	56.20	56.55	0.35	<.001	0.001	0.01	0.01	<2	<.001	<.001	0.06	0.93	<.01	0.003	<.001	0.001
CMC 05-12	25838	56.55	58.75	2.20	<.001	0.001	<.01	0.02	<2	0.001	0.001	0.16	2.4	<.01	0.007	<.001	<.001
CMC 05-12	25839	58.75	60.75	2.00	<.001	0.021	0.13	1.72	53	<.001	0.001	0.66	2.58	<.01	0.002	0.006	0.001
CMC 05-12	25840	60.75	62.65	1.90	<.001	0.001	0.07	0.3	5	<.001	<.001	1.13	3.14	<.01	0.001	0.001	<.001
CMC 05-12	25841	62.65	63.60	0.95	0.003	0.001	0.05	0.13	5	<.001	0.001	0.67	2.6	0.25	0.001	<.001	<.001
CMC 05-12	25842	63.60	64.30	0.70	0.001	0.004	0.03	0.73	4	<.001	0.001	0.9	3.44	0.09	0.001	0.002	<.001
CMC 05-12	25843	64.30	65.30	1.00	0.001	0.001	0.05	0.28	<2	<.001	<.001	1.13	3.86	<.01	0.001	0.001	<.001
CMC 05-12	25844	65.30	67.40	2.10	<.001	<.001	0.05	0.15	3	<.001	<.001	0.37	2.1	<.01	0.008	<.001	<.001
CMC 05-13	25845	0.00	0.70	0.70	<.001	0.01	0.1	0.23	31	<.001	<.001	0.72	2.12	<.01	0.002	0.001	0.002
CMC 05-13	25846	0.70	1.23	0.53	0.001	0.024	0.14	0.24	45	<.001	<.001	0.45	2.89	0.01	0.001	0.001	0.007
CMC 05-13	25847	1.23	1.58	0.35	<.001	0.609	8.78	1.81	4898	<.001	<.001	0.14	0.95	0.04	<.001	0.018	0.628
CMC 05-13	25848	1.58	1.92	0.34	<.001	0.519	8.73	2.09	4759	<.001	<.001	0.04	0.54	0.03	<.001	0.012	0.562
CMC 05-13	25849	1.92	2.42	0.50	<.001	0.015	0.13	0.11	14	<.001	<.001	0.13	1.54	0.01	0.001	0.003	0.019
CMC 05-13	25850	2.42	3.00	0.58	<.001	0.07	0.51	0.77	412	<.001	<.001	0.08	1.38	0.02	0.001	0.021	0.055
CMC 05-13	25851	3.00	4.00	1.00	0.002	0.015	0.34	0.39	98	<.001	<.001	0.2	1.57	0.01	0.001	0.004	0.011
CMC 05-13	25852	4.00	5.00	1.00	0.006	0.004	0.02	0.2	10	<.001	<.001	0.27	1.72	<.01	0.001	0.002	0.002
CMC 05-13	25853	5.00	6.00	1.00	0.005	0.004	0.03	0.19	18	<.001	<.001	0.48	2.37	0.01	0.001	0.001	0.004
CMC 05-13	25854	N/A	N/A	N/A	0.076	0.884	0.14	0.08	831	<.001	<.001	0.02	1.46	0.05	0.008	0.001	0.203
CMC 05-13	25855	6.00	7.40	1.40	<.001	0.006	0.05	0.38	10	<.001	<.001	0.72	2.21	<.01	0.001	0.001	0.003
CMC 05-13	25856	7.40	8.05	0.65	<.001	0.008	0.18	1.25	18	<.001	<.001	0.78	1.96	<.01	0.001	0.003	0.003
CMC 05-13	25857	8.05	8.80	0.75	<.001	0.006	0.05	0.67	18	<.001	<.001	0.28	1.01	<.01	0.001	0.001	0.001
CMC 05-13	25858	8.80	9.00	0.20	<.001	0.003	0.02	0.69	3	0.005	0.003	0.35	5.04	<.01	0.006	0.002	0.002
CMC 05-13	25859	9.00	10.10	1.10	<.001	0.001	0.03	0.66	2	<.001	<.001	0.22	0.83	<.01	0.001	0.001	<.001
CMC 05-14	25860	N/A	N/A	N/A	<.001	0.001	<.01	<.01	<2	<.001	<.001	0.01	0.11	<.01	0.004	<.001	<.001
CMC 05-14	25861	8.35	9.85	1.50	<.001	0.005	0.01	0.05	<2	<.001	<.001	0.04	0.74	<.01	0.001	<.001	<.001
CMC 05-14	25862	9.85	11.35	1.50	<.001	0.007	0.01	0.05	4	<.001	<.001	0.03	0.81	<.01	0.001	<.001	0.001
CMC 05-14	25863	9.85	11.35	1.50	<.001	0.007	<.01	0.06	3	<.001	<.001	0.03	0.85	<.01	0.001	<.001	0.001
CMC 05-14	25864	11.35	12.85	1.50	<.001	0.003	<.01	0.03	2	<.001	<.001	0.03	0.87	<.01	0.003	<.001	0.001
CMC 05-14	25865	12.85	14.00	1.15	<.001	0.005	<.01	0.03	3	<.001	<.001	0.03	0.94	<.01	0.004	<.001	<.001
CMC 05-14	25866	14.00	15.20	1.20	0.001	0.013	0.02	0.14	18	<.001	<.001	0.24	1.42	<.01	0.001	0.001	0.001
CMC 05-14	25867	15.20	16.30	1.10	0.001	0.009	0.04	0.1	52	<.001	<.001	0.09	1.16	<.01	0.001	<.001	0.001
CMC 05-14	25868	16.30	17.30	1.00	0.001	0.023	0.08	0.15	211	<.001	<.001	0.03	1.92	0.02	<.001	0.001	0.008
CMC 05-14	25869	17.30	18.30	1.00	0.001	0.014	0.06	0.11	36	<.001	<.001	0.2	1.85	<.01	0.001	<.001	0.005
CMC 05-14	25870	18.30	20.00	1.70	<.001	0.004	0.02	0.79	5	<.001	<.001	0.1	0.92	<.01	0.001	0.001	0.002

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-12	25836	55.10	56.20	1.10	<.01	1.38	0.058	0.001	0.17	0.65	<.01	0.35	<.001	<.001	<.01	4.95
CMC 05-12	25837	56.20	56.55	0.35	<.01	1.03	0.058	0.001	0.12	0.61	<.01	0.25	<.001	<.001	<.01	1.52
CMC 05-12	25838	56.55	58.75	2.20	<.01	2.69	0.105	0.002	0.39	0.71	0.01	0.34	0.001	<.001	<.01	7.33
CMC 05-12	25839	58.75	60.75	2.00	<.01	0.48	0.054	<.001	0.17	0.41	<.01	0.4	<.001	<.001	0.01	7.1
CMC 05-12	25840	60.75	62.65	1.90	<.01	0.24	0.069	0.001	0.16	0.48	<.01	0.46	<.001	<.001	<.01	6.55
CMC 05-12	25841	62.65	63.60	0.95	<.01	0.35	0.049	0.001	0.08	0.32	<.01	0.32	<.001	<.001	0.16	5.33
CMC 05-12	25842	63.60	64.30	0.70	<.01	0.19	0.048	0.001	0.08	0.33	<.01	0.34	<.001	<.001	0.06	3.97
CMC 05-12	25843	64.30	65.30	1.00	<.01	0.26	0.074	<.001	0.17	0.41	<.01	0.42	<.001	<.001	<.01	5.58
CMC 05-12	25844	65.30	67.40	2.10	<.01	1.51	0.084	0.001	0.32	0.46	<.01	0.45	0.001	<.001	<.01	6.39
CMC 05-13	25845	0.00	0.70	0.70	<.01	0.12	0.058	<.001	0.03	0.37	<.01	0.36	<.001	<.001	<.01	1.71
CMC 05-13	25846	0.70	1.23	0.53	<.01	0.09	0.055	<.001	0.02	0.38	<.01	0.37	<.001	<.001	<.01	1.93
CMC 05-13	25847	1.23	1.58	0.35	<.01	0.01	0.007	<.001	0.01	0.13	<.01	0.12	<.001	<.001	0.12	1.85
CMC 05-13	25848	1.58	1.92	0.34	0.01	0.02	0.012	<.001	0.01	0.16	<.01	0.15	<.001	<.001	0.19	1.39
CMC 05-13	25849	1.92	2.42	0.50	<.01	0.07	0.048	0.001	0.02	0.31	<.01	0.33	<.001	<.001	<.01	1.91
CMC 05-13	25850	2.42	3.00	0.58	<.01	0.07	0.045	<.001	0.03	0.4	<.01	0.36	<.001	<.001	0.05	1.37
CMC 05-13	25851	3.00	4.00	1.00	<.01	0.07	0.04	<.001	0.03	0.33	<.01	0.34	<.001	<.001	0.01	2.81
CMC 05-13	25852	4.00	5.00	1.00	<.01	0.1	0.053	0.001	0.03	0.34	<.01	0.37	<.001	<.001	<.01	4.67
CMC 05-13	25853	5.00	6.00	1.00	<.01	0.11	0.049	<.001	0.05	0.33	<.01	0.35	<.001	<.001	<.01	3.37
CMC 05-13	25854	N/A	N/A	N/A	0.01	0.49	0.008	0.003	0.09	0.2	0.02	0.13	<.001	0.001	0.1	-
CMC 05-13	25855	6.00	7.40	1.40	<.01	0.14	0.059	<.001	0.06	0.37	<.01	0.37	<.001	<.001	<.01	3.83
CMC 05-13	25856	7.40	8.05	0.65	<.01	0.16	0.059	<.001	0.06	0.35	<.01	0.37	<.001	<.001	<.01	2.71
CMC 05-13	25857	8.05	8.80	0.75	<.01	0.16	0.053	0.001	0.04	0.35	<.01	0.35	<.001	<.001	<.01	2.03
CMC 05-13	25858	8.80	9.00	0.20	<.01	1.38	0.271	0.006	0.65	2.61	0.01	0.26	0.001	<.001	<.01	0.52
CMC 05-13	25859	9.00	10.10	1.10	<.01	0.14	0.042	<.001	0.05	0.38	<.01	0.34	<.001	<.001	<.01	2.87
CMC 05-14	25860	N/A	N/A	N/A	<.01	20.67	0.001	<.001	11.7	0.01	<.01	0.01	0.001	<.001	<.01	5.1
CMC 05-14	25861	8.35	9.85	1.50	<.01	0.2	0.057	0.001	0.06	0.48	<.01	0.24	<.001	<.001	<.01	5.82
CMC 05-14	25862	9.85	11.35	1.50	<.01	0.2	0.045	<.001	0.08	0.48	0.01	0.22	0.001	<.001	<.01	4.81
CMC 05-14	25863	9.85	11.35	1.50	<.01	0.75	0.043	<.001	0.4	0.46	0.01	0.22	<.001	<.001	<.01	4.72
CMC 05-14	25864	11.35	12.85	1.50	<.01	0.54	0.038	0.001	0.11	0.46	0.02	0.23	<.001	<.001	<.01	6.17
CMC 05-14	25865	12.85	14.00	1.15	<.01	0.63	0.026	<.001	0.11	0.39	0.02	0.24	<.001	<.001	<.01	4.53
CMC 05-14	25866	14.00	15.20	1.20	<.01	0.07	0.025	0.001	0.03	0.32	<.01	0.36	<.001	<.001	<.01	5.14
CMC 05-14	25867	15.20	16.30	1.10	<.01	0.05	0.033	0.001	0.01	0.31	0.01	0.3	<.001	<.001	<.01	5.22
CMC 05-14	25868	16.30	17.30	1.00	<.01	0.03	0.021	<.001	0.01	0.29	<.01	0.3	<.001	<.001	0.01	2.08
CMC 05-14	25869	17.30	18.30	1.00	<.01	0.07	0.046	<.001	0.03	0.35	<.01	0.37	<.001	<.001	<.01	2.63
CMC 05-14	25870	18.30	20.00	1.70	<.01	0.12	0.044	0.001	0.03	0.4	0.01	0.34	<.001	<.001	<.01	6.45

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Mo %	Cu %	Pb %	Zn %	Ag** gm/mt	Ni %	Co %	Mn %	Fe %	As %	Sr %	Cd %	Sb %
CMC 05-14	25871	20.00	22.00	2.00	<.001	0.002	0.04	0.26	8	<.001	<.001	0.49	1.44	<.01	0.001	0.001	0.001
CMC 05-14	25872	22.00	22.45	0.45	<.001	0.002	0.05	0.09	13	<.001	<.001	0.15	1.13	<.01	0.001	<.001	0.002
CMC 05-14	25873	22.45	23.15	0.70	<.001	0.001	0.02	0.19	3	<.001	<.001	0.37	1.72	<.01	0.001	0.001	<.001
CMC 05-14	25874	23.15	23.35	0.20	0.001	0.001	0.04	0.22	4	<.001	<.001	0.27	1.69	0.01	0.001	0.001	0.002
CMC 05-14	25875	23.35	23.50	0.15	0.002	0.588	4.81	44.26	2654	<.001	0.002	0.04	1.66	0.23	<.001	0.093	0.289
CMC 05-14	25876	23.50	23.65	0.15	<.001	0.006	0.05	1.49	15	0.004	0.002	0.4	2.79	0.01	0.007	0.002	0.003
CMC 05-14	25877	23.65	23.95	0.30	<.001	0.003	0.02	0.24	12	<.001	<.001	0.21	1.01	0.01	0.001	0.001	0.002
CMC 05-14	25878	23.95	24.95	1.00	<.001	0.001	0.03	0.21	2	0.001	<.001	0.46	1.76	<.01	0.002	<.001	<.001
CMC 05-14	25879	24.95	26.80	1.85	<.001	0.002	0.05	0.32	11	<.001	<.001	0.07	0.97	<.01	0.005	<.001	0.002
CMC 05-14	25880	26.80	28.80	2.00	<.001	<.001	<.01	0.58	<2	<.001	<.001	0.08	0.87	<.01	0.003	<.001	<.001
CMC 05-14	25881	28.80	30.80	2.00	<.001	0.003	0.03	0.24	12	<.001	<.001	0.4	1.63	<.01	0.003	<.001	0.001
CMC 05-14	25882	30.80	32.80	2.00	<.001	0.001	<.01	0.42	<2	<.001	<.001	0.07	0.82	<.01	0.003	<.001	<.001
CMC 05-14	25883	32.80	34.80	2.00	<.001	0.003	0.02	0.19	4	<.001	<.001	0.26	1.36	<.01	0.002	<.001	0.001
CMC 05-14	25884	N/A	N/A	N/A	0.073	0.872	0.13	0.08	835	<.001	<.001	0.02	1.46	0.05	0.008	0.001	0.207
CMC 05-14	25885	34.80	35.55	0.75	0.001	0.01	0.03	0.21	16	<.001	<.001	0.45	1.64	<.01	0.002	<.001	0.002
CMC 05-14	25886	38.10	40.10	2.00	<.001	0.004	<.01	0.11	<2	<.001	<.001	0.03	1.37	<.01	0.004	<.001	0.001
CMC 05-14	25887	50.30	51.20	0.90	<.001	0.004	<.01	0.03	<2	<.001	<.001	0.06	0.97	<.01	0.005	<.001	0.001
CMC 05-14	25888	N/A	N/A	N/A	<.001	<.001	<.01	<.01	<2	<.001	<.001	0.01	0.09	<.01	0.004	<.001	<.001
CMC 05-14	25889	51.20	52.70	1.50	<.001	0.007	<.01	0.01	<2	<.001	<.001	0.03	0.76	<.01	0.004	<.001	0.001
CMC 05-14	25890	52.70	54.30	1.60	<.001	0.016	0.01	0.05	5	<.001	<.001	0.1	1.12	<.01	0.002	<.001	0.001
CMC 05-14	25891	54.30	55.05	0.75	<.001	0.007	0.01	0.04	4	<.001	<.001	0.1	0.74	<.01	0.003	<.001	0.001
CMC 05-14	25892	55.05	56.65	1.60	0.001	0.003	0.02	0.07	3	<.001	<.001	0.4	1.36	<.01	0.002	<.001	0.001
CMC 05-14	25893	55.05	56.65	1.60	0.001	0.002	0.03	0.11	2	<.001	<.001	0.46	1.41	<.01	0.001	<.001	<.001
CMC 05-14	25894	56.65	58.15	1.50	<.001	0.001	<.01	<.01	<2	<.001	<.001	0.09	0.95	<.01	0.009	<.001	0.001
CMC 05-14	25895	58.15	59.65	1.50	0.001	0.001	<.01	<.01	<2	<.001	<.001	0.06	0.91	<.01	0.008	<.001	<.001
CMC 05-14	25896	59.65	61.45	1.80	0.002	<.001	0.01	0.04	<2	<.001	<.001	0.13	1.1	<.01	0.012	<.001	0.001
CMC 05-14	25897	61.45	63.45	2.00	<.001	0.001	0.01	0.05	<2	<.001	<.001	0.23	2.13	<.01	0.011	<.001	0.002
CMC 05-14	25898	63.45	66.45	3.00	0.001	0.001	0.03	0.13	<2	<.001	<.001	0.47	2.32	0.01	0.005	<.001	0.001
CMC 05-14	25899	66.45	68.45	2.00	0.001	0.002	<.01	<.01	<2	<.001	<.001	0.09	1.89	<.01	0.01	<.001	0.001
CMC 05-14	25900	68.45	69.50	1.05	<.001	0.001	<.01	0.01	<2	<.001	<.001	0.08	1.56	<.01	0.012	<.001	<.001

Drill Hole	Sample #	From (m)	To (m)	Length (m)	Bi %	Ca %	P %	Cr %	Mg %	Al %	Na %	K %	W %	Hg %	Au** gm/mt	Sample kg
CMC 05-14	25871	20.00	22.00	2.00	<.01	0.14	0.053	<.001	0.04	0.36	<.01	0.39	<.001	<.001	<.01	8.22
CMC 05-14	25872	22.00	22.45	0.45	<.01	0.07	0.03	0.001	0.02	0.3	<.01	0.31	<.001	<.001	0.01	1.85
CMC 05-14	25873	22.45	23.15	0.70	<.01	0.12	0.048	<.001	0.05	0.37	<.01	0.41	<.001	<.001	<.01	2.05
CMC 05-14	25874	23.15	23.35	0.20	<.01	0.1	0.041	<.001	0.03	0.32	<.01	0.33	<.001	<.001	0.01	1.01
CMC 05-14	25875	23.35	23.50	0.15	<.01	<.01	0.001	<.001	<.01	0.08	<.01	0.05	<.001	0.003	0.22	0.97
CMC 05-14	25876	23.50	23.65	0.15	<.01	1.58	0.264	0.006	0.68	3.73	0.01	0.22	<.001	<.001	<.01	0.42
CMC 05-14	25877	23.65	23.95	0.30	<.01	0.1	0.041	<.001	0.03	0.33	<.01	0.38	<.001	<.001	0.01	1.39
CMC 05-14	25878	23.95	24.95	1.00	<.01	0.35	0.059	0.001	0.09	0.41	<.01	0.41	0.001	<.001	<.01	4.41
CMC 05-14	25879	24.95	26.80	1.85	<.01	0.81	0.051	<.001	0.12	0.42	<.01	0.37	<.001	<.001	<.01	4.35
CMC 05-14	25880	26.80	28.80	2.00	<.01	0.58	0.048	0.001	0.09	0.41	0.01	0.36	<.001	<.001	0.01	7.21
CMC 05-14	25881	28.80	30.80	2.00	<.01	0.48	0.055	<.001	0.1	0.48	0.01	0.44	<.001	<.001	0.01	7.91
CMC 05-14	25882	30.80	32.80	2.00	<.01	0.49	0.05	<.001	0.09	0.39	<.01	0.32	<.001	<.001	0.01	5.83
CMC 05-14	25883	32.80	34.80	2.00	<.01	0.5	0.055	0.001	0.1	0.41	<.01	0.34	<.001	<.001	<.01	7.56
CMC 05-14	25884	N/A	N/A	N/A	<.01	0.51	0.008	0.003	0.09	0.2	0.02	0.14	<.001	<.001	0.1	-
CMC 05-14	25885	34.80	35.55	0.75	<.01	0.4	0.06	<.001	0.08	0.4	<.01	0.41	<.001	<.001	0.01	3.37
CMC 05-14	25886	38.10	40.10	2.00	<.01	0.6	0.051	<.001	0.22	0.8	0.03	0.25	<.001	<.001	0.01	6.45
CMC 05-14	25887	50.30	51.20	0.90	<.01	1.35	0.026	<.001	0.13	0.56	<.01	0.31	<.001	<.001	<.01	3.26
CMC 05-14	25888	N/A	N/A	N/A	<.01	19.89	0.002	<.001	11.47	0.02	<.01	0.01	<.001	<.001	<.01	4.65
CMC 05-14	25889	51.20	52.70	1.50	<.01	0.99	0.021	<.001	0.11	0.42	<.01	0.22	<.001	<.001	<.01	5.41
CMC 05-14	25890	52.70	54.30	1.60	<.01	0.54	0.028	<.001	0.05	0.28	<.01	0.28	<.001	<.001	<.01	5.56
CMC 05-14	25891	54.30	55.05	0.75	<.01	1.66	0.018	<.001	0.25	0.25	<.01	0.27	<.001	<.001	0.01	2.29
CMC 05-14	25892	55.05	56.65	1.60	<.01	0.88	0.017	<.001	0.04	0.28	<.01	0.28	0.001	<.001	0.01	3.37
CMC 05-14	25893	55.05	56.65	1.60	<.01	0.69	0.017	<.001	0.04	0.21	<.01	0.24	<.001	<.001	<.01	3.17
CMC 05-14	25894	56.65	58.15	1.50	<.01	1.74	0.052	<.001	0.08	0.5	<.01	0.37	<.001	<.001	0.01	4.7
CMC 05-14	25895	58.15	59.65	1.50	<.01	1.74	0.051	<.001	0.07	0.54	<.01	0.3	<.001	<.001	0.01	5.53
CMC 05-14	25896	59.65	61.45	1.80	<.01	2.79	0.053	<.001	0.1	0.53	<.01	0.32	<.001	<.001	0.01	6.49
CMC 05-14	25897	61.45	63.45	2.00	<.01	2.55	0.069	<.001	0.32	0.42	<.01	0.33	<.001	<.001	<.01	8.39
CMC 05-14	25898	63.45	66.45	3.00	<.01	1.21	0.07	<.001	0.2	0.46	<.01	0.41	<.001	<.001	0.01	11.83
CMC 05-14	25899	66.45	68.45	2.00	<.01	1.98	0.079	<.001	0.27	0.68	0.01	0.36	<.001	<.001	0.01	7.85
CMC 05-14	25900	68.45	69.50	1.05	<.01	2.1	0.077	0.001	0.34	0.49	0.01	0.37	<.001	<.001	<.01	4.38