

**REPORT ON THE
2007 DIAMOND DRILLING PROGRAM
on the TYPHOON PROPERTY**

CLEAR CREEK AREA, YUKON

On Quartz claims:

Claim	Grant #
Bell 10 - 24	YC20885 - YC20899
Blue 1 - 4	YC21554 - YC21557
Wind 1 - 3	YC28846 - YC28848
Zephyr 1 - 3	YC28849 - YC28851
Storm 1 - 3	YC28852 - YC28854
Gale 1 - 3	YC28855 - YC28857
Breeze 1 - 8	YC34617 - YC34624
Blizzard 1 - 16	YC35578 - YC35593
Squall 1 - 62	YC36582 - YC36643

For assessment work performed
May 31 to October 6, 2007

For
Curlew Lake Resources Inc.
Suite 104, 20641 Logan Avenue
Langley, BC, V3A 7R3

Report By
J. Michael Wark B.Sc.(Hons)
Aurora Geosciences Ltd
34A Laberge Road
Whitehorse, Yukon, Y1A 5Y9

Location: Latitude 63° 49' 30"N, Longitude 137° 20' 00"W
Mining District: Dawson
NTS: 115P/14
Date: March 13, 2008

TABLE of CONTENTS

	Summary	
1.0	Introduction.....	1
2.0	Property Location and Access.....	1
3.0	Claim Information.....	2
4.0	Physiography and Climate.....	2
5.0	History.....	3
6.0	Regional Geological Setting.....	4
7.0	2007 Exploration Program.....	5
8.0	Conclusions.....	6
9.0	Recommendations.....	7
10.0	Statement of Expenditures.....	8
11.0	References.....	9

Figures

1	Property Location Map.....	Following page 1
2	Claim Location Map.....	Following page 1
3	Regional Geology Map.....	Following page 4
4	Compilation Map.....	Map Pocket

Appendices

Appendix I	Statement of Qualifications
Appendix II	Diamond Drill Log DDH-2007-CWQ-06
Appendix III	Assay Certificates
Appendix IV	Analytical Procedures
Appendix V	Claim Data

SUMMARY

Curlew Lake Resources Inc. retained Aurora Geosciences Ltd. to conduct geophysical surveys, soil sampling, and diamond drilling supervision on the Typhoon property in the Clear Creek area, Yukon. The crew mobilized to the property on May 31st to establish a base camp and all exploration and diamond drilling activity was completed by October 6th when the camp was dismantled and demobilized to Whitehorse.

The field exploration program comprised 14.53 line-km of line cutting, 14.97 line-km of IP surveying, six line-km of GPS controlled flagged grid for soil sampling and a ground magnetics survey, prospecting, trenching, and completion of six diamond drill holes totalling 1001.69 metres.

This report documents results of a single drill hole on the Squall 6 claim (DDH-2007-CWQ-06) for assessment purposes and only briefly summarizes the remainder of work completed.

The Typhoon property is situated within the Tombstone Gold Belt, which is one of several mineral districts that comprise the Tintina Gold Province. The Tombstone Gold Belt is the type area for the intrusion-related gold system (IRGS) mineral deposit model. Gold deposits and occurrences within the Tombstone Gold Belt are directly associated with numerous mid-Cretaceous plutons, sills, and dykes that intrude along the northern margin of the Selwyn Basin in central Yukon.

The Typhoon property encompasses portions of Left Clear Creek, Bell Creek and the entire drainage of 65 Pup. Bell Creek and 65 Pup are tributaries to Left Clear Creek. Placer gold mining in Clear Creek extends back to 1900, when the discovery claim was staked. Since 1941, the Clear Creek area has reported gold production of about 129,000 crude ounces, including 49,637 ounces recovered from dredging operations (As of 1999).

The Typhoon property consists of 117 Quartz Mining Claims and the focus of exploration has been to locate a potential lode source for the placer gold mineralization in the area. Several intrusion-related, gold-tungsten and gold-tin, as well as a gold-in-quartz occurrence have been documented immediately east of the Typhoon property; these are all associated with mid-Cretaceous intermediate plutons and stocks of the Mayo plutonic suite.

Gold deposits in the region such as Dublin Gulch, Scheelite Dome and Clear Creek, as well as the Fort Knox deposit in Alaska, all represent type examples of the intrusion-related gold system.

Assay results from DDH-2007-CWQ-06 indicate the hole failed to intersect any significant gold mineralization and did not encounter any intrusive rocks. The hole location was selected to test an IP anomaly with high chargeability and low resistivity.

1.0 INTRODUCTION

In 2007, Curlew Lake Resources Inc. contracted Aurora Geosciences Ltd. to conduct an exploration program of line cutting, geophysical surveying (IP and Magnetics), soil sampling, and diamond drilling supervision on the Typhoon property in the Clear Creek area, Yukon. The crew mobilized to the property on May 31st to establish a base camp and all exploration and diamond drilling activity was completed by October 6th when the camp was dismantled and demobilized to Whitehorse.

Diamond drilling operations were contracted to E. Caron Diamond Drilling Limited of Whitehorse, Yukon. The drill contractor mobilized to the property on July 7, 2007 and demobilized to Whitehorse on September 28, 2007. A total of six NQ diameter holes were completed for a total of 1001.69 m of drilling.

Exploration work conducted by Aurora Geosciences Ltd. included 14.53 line-km of line cutting and giddying, 14.975 line-km of IP/Resistivity survey, and establishment of 6.0 line-km of GPS controlled grid over which ground magnetics and soil geochemical surveys were completed. A total of 122 soil samples were collected at 100 x 50 metre spacing. A limited prospecting and lithochemical program was also undertaken.


This report has been prepared solely for mining assessment purposes and documents only the results of drilling from DDH-2007-CWQ-06. This drill hole is located on the Squall 6 claim (Figure 3) and was completed to a depth of 148.13 metres.

2.0 PROPERTY LOCATION and ACCESS

The Typhoon property is located about 360 km north of Whitehorse, 75 km west-northwest of Mayo, and 105 km east-southeast of Dawson City, Yukon. The claims straddle a portion of Left Clear Creek and entirely include 65 Pup and its drainage, a small tributary of Left Clear Creek. All the claims are situated on NTS map sheet 115P/14 and centred at about 63° 49' 30" N latitude and 137° 20' 00" W longitude (Figures 1 and 2).

The project area is accessible by the Barlow Dome Road, a narrow gravel road that runs along the ridge on the north side of Clear Creek from the North Klondike Highway near Barlow Lake, for approximately 20 km to the property area. During summer months, it is possible to drive a passenger car as far as Left Clear Creek; further access is possible with 4-wheel drive truck.


The land on which the mineral claims are located is Crown Land and falls under jurisdiction of the government of the Yukon. First Nation Settlement Land areas, surface rights for which belong to the Tr'ondek Hwech'in First Nation, lie three kilometres northwest of the claims on the north side of the Barlow Dome road.



**CURLEW LAKE RESOURCES LTD
TYPHOON PROPERTY
Figure 1 - Location Map**

December 31, 2007

AURORA GEOSCIENCES LTD



Curlew Lake Resources claims

**CURLEW LAKE RESOURCES LTD
TYPHOON PROPERTY**

Figure 2 - CLAIM LOCATION MAP

NTS 115P14

Mining District: Dawson

Datum: NAD83

Projection: UTM, zone 8

Date: January 1, 2008

Job: CWQ-06-01-YT

scale 1:25,000

AURORA GEOSCIENCES LTD

3.0 CLAIM INFORMATION

As of 2007, the Typhoon property consisted of 117 Yukon quartz mineral claims. A 100% working interest on 98 of these claims, held by Curlew Lake Resources Inc., is subject to a 4% Net Smelter Royalty (NSR), of which 1% may be purchased by Curlew Lake at any time in the future for the price of \$600,000 in cash or shares, and an additional 2% may be purchased at any time for \$1,000,000 in cash.

Following an exploration program on the property in the summer of 2006, Curlew Lake signed an option agreement with Xenex Development Corp. to acquire 19 Blue and Bell quartz claims immediately adjoining the Typhoon property to the west. A 100% working interest on these 19 claims requires \$20,000 in further cash payments over the next two years. Curlew Lake is also required to complete a work program on these 19 claims at a cost of not less than \$60,000 over 3 years. Xenex will retain a 2% NSR which may be purchased at any time by Curlew Lake for \$1,000,000 for each 1%.

All claims are located on NTS map sheet 115P/14 and are in the Dawson Mining District. The claims are plotted on Figure 2. Claim information is included in Appendix IV.

The claims are in good standing with expiry dates as shown in Schedule A (Appendix IV). The expiry dates listed in Schedule A do not reflect the 2007 exploration work being submitted for assessment credits with this report.

4.0 PHYSIOGRAPHY and CLIMATE

The project area is in the Syenite Range Mountains on the north side of the Tintina Trench. The property covers a ridge in gentle rounded mountainous terrain. Elevations range from about 2000 feet to 4000 feet above sea level. The property area is moderately well-treed, with spruce, pine, birch, alder, and locally with considerable buck brush.

The area experiences cold dry winters and hot dry summers. Snow usually begins accumulating in late September or early October and is generally melted by late May to early June. Temperatures range from highs in the mid 30°'s in summer to lows of -50° C in winter. North facing slopes are generally underlain by permafrost.

The nearest major city centre is Dawson, a supply centre for this region with an ample labour force. Power is available along the North Klondike Highway. Water resources are abundant in the project area in flowing streams.

5.0 HISTORY

The Clear Creek area has a long history of placer gold production and mineral exploration for silver, gold, antimony, copper, tin and tungsten. The majority of work has been conducted on the Clear Creek property located on Left Clear Creek, immediately east of the Typhoon property.

In 1971, a joint venture between Silver Standard Mines Ltd and Canada Tungsten Mining Corp staked claims following the release of GSC Open File 51 that indicated anomalous values for tungsten, gold and tin in the area. United Keno Hill Mines Ltd and Standard Oil Company of B.C. Ltd also acquired land in the area during this time. The staking generally occurred in the Left Clear Creek area. These companies conducted soil sampling and geological mapping programs on their properties.

In 1978 and 1979, Cominco Ltd conducted programs of stream sediment sampling, soil sampling and prospecting on their NEL claims at the headwaters of Forty Mile Creek, 20 km to the northeast of the Typhoon Property. This work focussed on anomalous tin and silver values indicated from government regional stream sediment geochemical samples in the area.

Cominco obtained very anomalous Sn values, up to 18,100 ppm, from stream sediment samples.

In 1980 – 81, Canada Tungsten Mining Corporation Ltd. acquired large blocks of claims through staking and options in the Dublin Gulch and Clear Creek areas and carried out extensive programs in search of tungsten and, to a much lesser extent, tin and gold. On Left Clear Creek, Canada Tungsten completed extensive mapping and geochemical surveys. Some trenching and sampling was done on tungsten bearing skarns but no work was done to follow up on geochemical gold anomalies. The original claim group was gradually reduced to the Rain and Wind claims, which consisted of several non-contiguous claims covering various mineral showings and anomalies. Canada Tungsten later dropped its option.

In 1986, prospector Scottie Thom discovered gold-bearing massive pyrite float on the south side of Left Clear Creek. In 1987, placer operations conducted by Blackstone Placer Mining Company encountered heavy pyrite mineralization in a deep trench cutting into bedrock. The showing and properties were later optioned by Secret Pass Minerals Corp and, in 1987, they conducted a program of line cutting, geophysical surveying, soil and rock sampling. The property was later optioned to Cambridge Resources Ltd, who in 1989 conducted trenching and drilled 276 m in 4 diamond drill holes. The drill program encountered one significant intersection containing 0.546 oz/t gold over 0.49 m.

In 1995, Kennecott Canada Inc optioned the Clear Creek property and conducted an extensive program of soil sampling, geological mapping, trenching, road construction and reverse circulation drilling on the Rhosgobel Stock. Kennecott dropped its option later that year. In 1996, New Millennium Mining Inc acquired the project and in the fall 2004 it signed a

deal to vend the project to Stratagold Corp.

In 2004, Curlew Lake conducted a soil sample survey on the central portion of the Typhoon property. The following year they optioned the property to Select Resources Corporation. Select expanded the soil sampling survey eastward and conducted a magnetic survey on the expanded grid area. The program returned two weak magnetic highs on the western part of the survey area and a few scattered anomalous gold values as high as 342 ppb Au. In early 2006, Select decided not to continue with the option and returned the property to Curlew Lake.

In 2005, Mr Adamson optioned the Blue and Bell claims to Electrum Mining Ltd. Later that year Electrum conducted a soil sampling and magnetic survey on the property. The program identified a large magnetic high centered on the property and a few scattered weakly anomalous gold-in-soil values, the highest being 20 ppb.


6.0 REGIONAL GEOLOGICAL SETTING

The Typhoon Property lies within the Selwyn Basin, which is comprised of Late Proterozoic to Mid-Paleozoic continental margin sediments. The basinal rocks in the area of the property consist of an inlier of Upper Proterozoic to Lower Cambrian rocks of the Hyland Group overlain by Upper Cambrian and Ordovician Rabbitkettle Formation, which is in turn overlain by the Ordovician to Lower Silurian Road River Group and capped by the Devonian to Mississippian Earn Group.

The Hyland Group (**PCH**) is comprised of thin to thick bedded, brown to pale green shale, fine to coarse grained quartz-rich sandstone, quartz pebble conglomerate, argillaceous limestone, phyllite, psammite and minor marble (Gordey, et. al., 1999). The Rabbitkettle Formation (**COR**) consists of thin bedded, wavy banded, silty limestone and grey lustrous calcareous phyllite, limestone breccia and conglomerate, laminated grey siltstone, chert, slate and local mafic flows, breccia and tuff. The Road River Group (**ODR**) is comprised of black graptolitic shale and chert, minor argillaceous limestone and dolomitic siltstone. The Earn Group (**DME**) consists of thin-bedded slate with interbedded chert-quartz arenite and wacke, chert pebble conglomerate, black siliceous siltstone, nodular and bedded barite and rare limestone.

The layered rocks are intruded by mid-Cretaceous Tombstone Suite intrusions to the north and east and by lower Cretaceous McQuesten Suite intrusions to the south. Two types of Tombstone Suite intrusion are recognized in the area; medium to coarse-grained biotite-hornblende-clinopyroxene syenite, quartz syenite, granite, monzogranite, diorite and tinguaitite (**mKyT**); and medium- to coarse-grained, locally porphyritic biotite hornblende, clinopyroxene quartz monzonite and granodiorite (**mKqT**). The McQuesten Suite is comprised of medium- to coarse-grained, locally porphyritic and k-feldspar megacrystic biotite ± muscovite granite and quartz monzonite.

The Clear Creek area lies within the Tintina Gold Province, an intrusion-related, gold-bearing system that stretches in an arc from central Alaska through to southern Yukon. In the Yukon,



GEOLOGICAL LEGEND

- mKqT** mid Cretaceous
Tombstone Suite quartz-monzonite

- LKqM** Lower Cretaceous
Two Sisters Batholith quartz monzonite

- DME** Devonian to Mississippian
Earn Group sediments

- COR** Cambrian to Ordovician
Rabbitkettle Formation sediments

- PCH** Upper Proterozoic to Lower Cambrian
Hyland Group meta-sediments

scale 1:100,000

**CURLEW LAKE RESOURCES LTD
TYPHOON PROPERTY
Figure 3 - REGIONAL GEOLOGY MAP**

NTS 115P14

Datum: NAD83

Date: January 1, 2008

Mining District: Dawson

Projection: UTM, zone 8

Job: CWQ-06-01-YT

AURORA GEOSCIENCES LTD

this belt is known as the Tombstone-Tungsten Magmatic Belt. Within this belt many gold discoveries are spatially related to mid-Cretaceous, alkalic, plutonic intrusions of the Tombstone series. A wide variety of disseminated, skarn and vein-type mineral occurrences, both within and near the intrusions, have been identified that contain gold, tungsten, lead, zinc, copper and tin. The most significant discovery in the Clear Creek area is the Dublin Gulch Deposit, located 80 km east of the Red Rose Property. The Dublin Gulch deposit has reserves of 50.8 million tonnes containing 0.93 g/t gold. Other Tintina Gold Belt occurrences in the area are the Clear Creek property, located 8 km east of the Typhoon property, and the Scheelite Dome property located 55 km to the east. The Clear Creek area also has a long history of placer gold production.

No significant or economic-grade mineralization has been discovered to date on the Typhoon property, however, in the Left Clear Creek valley, a number of quartzite boulders have been discovered containing abundant pyrite in quartz-sericite-clay altered rocks. On the Clear Creek property, scheelite and auriferous arsenopyrite are found in quartz veined granite stocks at the Rhosgobel, Josephine, Lewis and Pukelman minifile occurrences. Scheelite and molybdenite are also found in sheeted quartz and potassium feldspar veins at Pukelman. The Typhoon property has not been subject to any detailed property scale mapping.

7.0 2007 EXPLORATION PROGRAM

In 2007, Curlew Lake Resources Inc. contracted Aurora Geosciences Ltd. to conduct an exploration program that consisted of line cutting, geophysical surveying (IP and Magnetics), soil sampling, and diamond drilling supervision on the Typhoon property. The crew mobilized to the property on May 31st to establish a base camp and all exploration and diamond drilling activity was completed by October 6th when the camp was dismantled and demobilized to Whitehorse.

Diamond drilling operations were contracted to E. Caron Diamond Drilling Limited of Whitehorse, Yukon. The drill contractor mobilized to the property on July 7, 2007 and demobilized to Whitehorse on September 28, 2007. A total of six NQ diameter holes were completed for a total of 1001.69 m of drilling.

Exploration work conducted by Aurora Geosciences Ltd. included 14.53 line-km of line cutting and gridding, 14.975 line-km of IP/Resistivity survey, and establishment of 6.0 line-km of GPS controlled grid over which ground magnetics and soil geochemical surveys were completed. A total of 122 soil samples were collected at 100 x 50 metre spacing. A limited prospecting and litho-geochemical program was also undertaken.

This report has been prepared solely for mining assessment purposes and documents only the results of drilling from DDH-2007-CWQ-06. This hole is located on the Squall 6 claim (Figure 3) and was completed to a depth of 148.13 metres.

Although only the results from a single diamond drill hole are discussed in this report, the location of the four cut grid lines, the flagged soil sample/magnetics grid (Ladder Zone), and

the location for all the drill holes is shown on Fig 3. Additionally, an IP profile was completed along the Barlow Dome roadside that covered portions of the Squall 4, 6, 8 and Breeze 1 claims. The results from this roadside IP "line" were used to spot two diamond drill holes on the Squall 6 claim ; DDH-2007-CWQ-05 and DDH-2007-CWQ-06.

All core logging and sampling was done from a base camp located on the old placer tailings on the east side of Left Clear Creek on the Blizzard 16 claim. The camp location is shown in Fig 3. With the exception of DDH-2007-CWQ-03, all remaining diamond drill core stored at the campsite was cross-piled, covered, and nailed securely shut upon demobilization. The core from DDH-2007-CWQ-03 was transported to Whitehorse for storage in the government core library.

DDH-2007-CWQ-06 was drilled on the south side of the Barlow Dome road (Fig 3) to test an IP anomaly with high chargeability and coincident low resistivity. This hole was drilled at an Azimuth of 130° to a depth of 148.13 metres at an inclination of 70° from horizontal. As the hole was logged, magnetic susceptibility measurements on the core were taken from each 3m run of core.

The drill log is included as Appendix II.

The drill core was sampled completely from top to bottom of the hole. All drill core was split with a diamond saw. One half the core was placed back in the core tray and the other half was placed in a sample bag for analysis.

All core samples were sealed and placed into polyweave (rice) bags for shipping. A record was maintained of the contents of each bag shipped and prior to shipment, each polyweave bag was securely closed with a numbered seal.

All core samples were transported from the project to Aurora Geosciences' warehouse in Whitehorse. From there, they were delivered to the Eco Tech Laboratory Ltd. sample preparation lab in Whitehorse. The sample pulps were forwarded to the Eco Tech assay lab in Kamloops, B.C.

The assay results are included as Appendix III. The sample sequence for this hole started at sample number 53935 and ended at sample number 54075. Each of the 140 samples was assayed for gold by the fire assay technique in addition to a 35 element ICP analysis.

8.0 CONCLUSIONS

DDH-2007-CWQ-06 intersected a monotonous sequence of interbedded phyllites, psammites and gritty psammite. These rock types have been correlated to the Yusezyu Formation of the Hyland Group. The predominant phyllites are strongly foliated and crenulated. Narrow, milky white quartz veins and veinlets were locally observed. Pyrite mineralization was seen to occur as fine grained, wispy lenses or disseminations and more rarely, on fractures, from about 74 to 100 metres.

This pyrite mineralization appears to account for the high chargeability/low resistivity IP anomaly.

No significant gold values were encountered. No Tombstone Suite intrusive rocks were observed in the drill core.

9.0 RECOMMENDATIONS

The Typhoon property has been explored in various stages since 2004 but this exploration program represents the first drilling attempts on the property. This report does not discuss the remaining work completed during 2007, however, it is strongly recommended that a complete review and evaluation of all available data be undertaken to produce property scale compilation map to assist in directing any further exploration work on the property.

10.0 STATEMENT of EXPENDITURES

A statement of expenditures for the entire 2007 exploration program is attached on the following page. For purposes of this assessment report, only those costs related to DDH-2007-CWQ-06 are to be considered for assessment credits on the property.

For this purpose, a drilling cost per metre was determined in the following manner. The total number of metres drilled was 1001.69 at an all in cost of \$426,190.63. This translates to an average cost per metre of \$425.47. DDH-2007-CWQ-06 was completed to a depth of 148.13 metres, therefore the calculated cost of this hole amounts to \$63,024.87.

Statement of Expenditures

Preparation, mobilization & demobilization:

Camp and equipment preparation	\$ 15,007.50	
Project management	<u>\$ 8,707.50</u>	
	\$ 23,715.00	\$ 23,715.00

Geology and Geophysical Surveys:

Line cutting and grid construction (14.53 km)	\$ 23,075.00	
Induced Polarization survey (14.97 km)	\$ 33,982.50	
Ground magnetics survey (6.0 km)	\$ 3,600.00	
Soil geochemical sampling (122 samples)	\$ 1,475.00	
Mapping/prospecting	\$ 15,420.00	
Expediting and support	\$ 29,785.00	
Project management	\$ 11,575.35	
Fuel expense	\$ 7,610.60	
Grocery expense	\$ 13,362.79	
Field supplies expense	\$ 7,601.33	
Prospecting assay expense	\$ 727.16	
Soil geochem assay expense	\$ 3,018.86	
Camp rental expense	\$ 24,900.00	
Accommodation and meals expense	\$ 209.17	
Vehicle rental expense	\$ 19,226.78	
Communication expense	\$ 1,225.00	
Computer rental expense	\$ 3,900.00	
Freight and cargo expense	<u>\$ 145.77</u>	
	\$200,840.31	\$ 200,840.31

Diamond Drilling:

Direct drilling cost (Caron Diamond Drilling)	\$246,951.98	
Project management and support	\$ 40,530.00	
Expediting and support	\$ 27,202.50	
Fuel expense	\$ 26,578.81	
Grocery expense	\$ 10,251.71	
Field supplies expense	\$ 3,493.69	
Core assay expense	\$ 23,140.75	
Camp rental expense	\$ 35,140.00	
Accommodation and meals expense	\$ 259.02	
Vehicle rental expense	\$ 8,625.00	
Communication expense	\$ 1,462.80	
Computer rental expense	\$ 2,460.00	
Freight and cargo expense	<u>\$ 94.37</u>	
	\$426,190.63	<u>\$ 426,190.63</u>
		\$ 650,745.94

I, J. Michael Wark, certify that, to the best of my knowledge, these expenditures are true and correct.

11.0 REFERENCES

Allen, T.L., Hart, C.J.R., and Marsh, E.E., 1999. Placer gold and associated heavy minerals of the Clear Creek drainage, central Yukon: Past to present. In: Yukon Exploration and Geology 1998, C.F. Roots and D.S. Emonds (eds.), Exploration and Geological Services Division, Yukon, Indian and Northern Affairs Canada, p. 197-214.

Hart, J.R., 2006. YGS Brochure 2006-6. Intrusion-Related Gold. Tombstone Gold Belt. Yukon Geological Survey.

Murphy, Donald C., 1997. Geology of the McQuesten River Region, Northern McQuesten and Mayo Map Areas, Yukon Territory (115P/14, 15, 16; 105M/13, 14). Exploration and Geological Services Division, Yukon, Indian and Northern Affairs Canada, Bulletin 6, 122 p.

Noyes, Harold J. et. al., 2006. Typhoon Project. Clear Creek Mining District, Yukon Territory. 2005 Annual Project Report. Internal assessment report prepared for Select Resources Corporation.

Appendix I

Statement of Qualifications

I, J. Michael Wark, B.Sc. (Hons), certify that:

- 1) I currently reside at 19 Turner Crescent, Whitehorse, Yukon Territory, Y1A 5R2
- 2) I am a graduate geologist currently employed by Aurora Geosciences Ltd. of Whitehorse, Yukon Territory.
- 3) I graduated from Dalhousie University in Halifax, Nova Scotia in 1980 with a Bachelor of Science Honours Degree in Geology.
- 4) Since my graduation I have practiced my profession continually.
- 5) I am currently a member in good standing with the Prospectors and Developers Association of Canada.
- 6) I have prepared this report based upon data collected by Aurora Geoscience employees from the Typhoon property, in addition to other third party, unpublished sources.
- 7) I have personally visited and supervised the exploration program on the Typhoon property in 2007.
- 8) I do not hold any shares or other interests of any type in Curlew Lake Resources Inc.
- 9) I am a past member of NAPEGG (Association of Professional Engineers, Geologists and Geophysicists of the NWT) and served the association as a counsellor and member of the disciplinary and membership committees.
- 10) I am unaware of any material fact or change with respect to the subject matter of this assessment report that is not reflected in the report, and the omission of which would cause this report to be misleading.

Dated this 17th day of March, 2008, at Whitehorse, Yukon Territory

J. Michael Wark, B.Sc. (Hons)

Appendix II

Curlew Lake Resources Inc. Clear Creek Typhoon Gold Project

Date Started: 2007 September 19

Date Completed: 2007 September 27

HOLE NUMBER: DDH-2007-CWQ-06

Hole Location: 383825 E
7080642 N

Hole Length: 148.13
Azimuth at Collar: 130
Inclination at Collar: -70
Overburden: 7.92 meters

GRID:

Section:
NTS: Refer to Report
Datum: NAD 83
Zone: Zone 08
Elevation: 1234 meters
Core Size: NQ
Logged By: Kel Sax

CONTRACTOR: E. Caron Diamond Drilling

SAMPLES COLLECTED: 140 Samples for Assay: 53935-54074

Prepared By:





-70 degrees

SCALE (meters) Lithology Structure 0 90 T.C.A.	Magnetic Susceptibility 0 1.0	LITHOLOGIC DESCRIPTION	Core Recovery	SAMPLE DATA
Sample No. From (m) To (m) Interval (m) Au (gpt) Ag (gpt)				

0.0		0.00 - 7.92 OVERBURDEN: Overburden									
10.0		7.92 - 36.50 GRITTY PSAMMITE: Scattered sand to pebble sized lithic fragments with chalky white feldspar crystals and rare grey blue quartz eyes, in medium grey, weakly but finely foliated psammite. Foliation is 45 degrees TCA. Occasional beds of dark grey contorted phyllite less than 10 cm. 11.25 - 12.0 white quartz vein with minor vugs and rusty fractures 12.9 - 24.8 quartz vein breccias to 20%	10								
			21								
			84	53935	7.92	9	1.08	<0.03	0.10		
			75	53936	9	10	1	<0.03	0.10		
			27	53937	10	11.25	1.25	<0.03	0.10		
			91	53938	11.25	12	0.75	<0.03	0.20		
			82	53939	12	12.9	0.9	<0.03	0.10		
			86	53940	12.9	14	1.1	<0.03	0.10		
			73	53941	14	15	1	<0.03	0.10		
			91	53942	15	16	1	<0.03	0.10		
			48	53943	16	17	1	<0.03	0.10		
			97	53944	17	17.8	0.8	<0.03	0.10		
			93	53945	17.8	18.45	0.65	<0.03	0.10		
			74	53946	18.45	19.5	1.05	<0.03	0.10		
			56	53947	19.5	20.5	1	<0.03	0.10		
			90	53948	20.5	21.5	1	<0.03	0.10		
			70	53949	21.5	22.5	1	<0.03	0.10		
			82	53950	22.5	23.5	1	<0.03	0.10		
			82	53951	23.5	24.5	1	<0.03	0.10		
			82	53952	24.5	25.5	1	<0.03	0.10		
			99	53953	25.5	26.5	1	<0.03	0.10		
			87	53954	26.5	27.5	1	<0.03	0.10		
			96	53955	27.5	28.5	1	<0.03	0.10		
			96	53956	28.5	29.5	1	<0.03	0.10		
			96	53957	29.5	30.5	1	<0.03	0.10		
			96	53958	30.5	31.5	1	<0.03	0.10		
			98	53959	31.5	32.5	1	<0.03	0.10		
			92	53960	32.5	33.5	1	<0.03	0.10		
			92	53961	33.5	34.5	1	<0.03	0.10		
			80	53962	34.5	35.5	1	<0.03	0.10		
			80	53963	35.5	36.5	1	<0.03	<0.1		

<p>SCALE (meters)</p> <p>Lithology Structure 0 90 T.C.A.</p>	<p>Magnetic Susceptibility 0 1.0</p>	<p>LITHOLOGIC DESCRIPTION</p>	<p>Core Recovery</p>	<p>SAMPLE DATA</p>
<p>Sample No. From (m) To (m) Interval (m) Au (gpt) Ag (gpt)</p>				





LITHOLOGIC DESCRIPTION


Core Recovery

SAMPLE DATA

Sample No. From (m) To (m) Interval (m) Au (gpt) Ag (gpt)

Depth (m)	Lithology Description	Core Recovery (%)	Sample No.	From (m)	To (m)	Interval (m)	Au (gpt)	Ag (gpt)
70.70 - 74.30	GRITTY PSAMMITE: Gritty psammite with rusty fractures perpendicular to foliation at 65 degrees TCA. Minor phyllite laminations.	98	53999	72.7	73.7	1	<0.03	0.20
		90	54000	73.7	74.3	0.6	<0.03	0.20
			54001	74.3	75.3	1	<0.03	0.10
74.30 - 81.50	CONTORTED PHYLLITE: Dark grey to black, contorted phyllite with wispy fine grained laminated pyrite to 5%, and erratic clasts to narrow beds gritty psammite. Minor, barren cross cutting quartz veinlets. Rare sheeted pyrite on some fractures. 76.6 - 76.96 crushed fault gouge.	89	54002	75.3	76.6	1.3	0.03	0.20
		94	54003	76.6	76.96	0.36	<0.03	0.10
			54004	76.96	78	1.04	<0.03	0.20
		90	54005	78	79	1	<0.03	0.20
			54006	79	80	1	<0.03	0.20
			54007	80	81	1	0.03	0.10
			54008	81	81.5	0.5	0.03	0.10
		95	54009	81.5	82.5	1	0.04	0.20
81.50 - 99.90	SIGMOIDEL PHYLLITE: Sigmoidal phyllite interbedded with psammite, bedding approximately 30 degrees, near isoclinally folded, non-parallel foliation at 70 to 80 degrees TCA. Trace to 2% pyrite clots and foliations in deformed quartz veinlets. 85.9 - 86.1 sheared fault with weak chlorite biotite alteration and minor barren quartz veining. 88.45 - 88.9 broken and crushed fault, poor recovery. 88.45 - 99.9 mottled orange and grey, sigmoidal phyllite with sericitic rusty fractures, laminations, and cross cutting seepage veinlets. Foliation 70 degrees TCA. 95.2 - 95.5 locally broken and sheared fault.	98	54010	82.5	83.5	1	<0.03	0.20
			54011	83.5	84.5	1	<0.03	0.10
		69	54012	84.5	85.5	1	0.03	0.10
			54013	85.5	86.5	1	0.04	0.10
			54014	86.5	87.5	1	<0.03	0.10
		75	54015	87.5	88.45	0.95	<0.03	0.10
			54016	88.45	90.2	1.75	0.06	0.10
		91	54017	90.2	91.2	1	<0.03	0.10
			54018	91.2	92.2	1	<0.03	0.10
		99	54019	92.2	93.2	1	<0.03	0.10
			54020	93.2	94.2	1	0.03	0.10
		63	54021	94.2	95.2	1	<0.03	0.10
		65	54022	95.2	95.5	0.3	<0.03	0.10
			54023	95.5	96.5	1	<0.03	0.10
		81	54024	96.5	97.5	1	<0.03	0.10
			54025	97.5	98.5	1	<0.03	0.10
		69	54026	98.5	99.5	1	<0.03	0.10
			54027	99.5	99.9	0.4	<0.03	0.10
		84	54028	99.9	100.9	1	<0.03	0.10
99.90 - 105.75	GRITTY PSAMMITE: Rusty, well foliated at 55 deg, gritty psammite with blue quartz eyes and sheared, weakly sericitic laminated phyllite.	77	54029	100.9	101.9	1	<0.03	0.10
		88	54030	101.9	102.9	1	<0.03	0.10
			54031	102.9	103.9	1	<0.03	0.10
		88	54032	103.9	104.9	1	<0.03	0.10
			54033	104.9	105.75	0.85	<0.03	0.10
105.75 - 117.70	QUARTZOFELDSPATHIC & MICACEOUS PSAMMITE: Weakly chloritic and sericitic phyllite, locally rusty and broken, with psammite and gritty psammite interbeds. 105.5 - 107.74 sandy fault.	52	54034	105.75	107.74	1.99	<0.03	0.10
		74	54035	107.74	108.62	0.88	<0.03	0.10

Total Depth = 148.13
 Hole Number: DDH-2007-CWQ-06



LITHOLOGIC DESCRIPTION

Core Recovery

SAMPLE DATA

Sample No. From (m) To (m) Interval (m) Au (gpt) Ag (gpt)

110.0		108.62 - 110.95 sandy fault	48	54036	108.62	109.5	0.88	<0.03	0.10
			97	54037	109.5	110.95	1.45	<0.03	0.10
			86	54038	110.95	112	1.05	<0.03	0.10
			74	54039	112	113.1	1.1	0.04	0.10
			22	54040	113.1	113.84	0.74	<0.03	0.10
			55	54041	113.84	114.9	1.06	<0.03	0.10
			84	54042	114.9	115.9	1	0.07	0.10
			94	54043	115.9	116.9	1	<0.03	0.10
			97	54044	116.9	117.7	0.8	<0.03	0.10
			90	54045	117.7	118.7	1	<0.03	0.10
			93	54046	118.7	119.7	1	<0.03	0.10
			86	54047	119.7	120.7	1	<0.03	0.10
			73	54048	120.7	121.7	1	<0.03	0.10
			84	54049	121.7	122.7	1	<0.03	0.10
			28	54050	122.7	123.7	1	<0.03	0.10
			71	54051	123.7	124.7	1	<0.03	0.10
			69	54052	124.7	125.7	1	<0.03	0.10
			57	54053	125.7	126.7	1	<0.03	0.10
				54054	126.7	127.7	1	<0.03	0.10
				54055	127.7	128.7	1	<0.03	0.10
				54056	128.7	129.7	1	<0.03	0.10
				54057	129.7	130.7	1	<0.03	0.10
				54058	130.7	131.68	0.98	<0.03	0.10
				54059	131.68	132.9	1.22	<0.03	<0.1
				54060	132.9	133.9	1	<0.03	0.10
				54061	133.9	134.9	1	<0.03	<0.1
				54062	134.9	135.9	1	<0.03	0.10
				54063	135.9	136.9	1	<0.03	0.10
				54064	136.9	138	1.1	<0.03	0.10
				54065	138	139	1	<0.03	0.10
				54066	139	140	1	<0.03	0.10
				54067	140	141	1	<0.03	0.10
				54068	141	142	1	<0.03	0.10
				54069	142	143	1	<0.03	0.10
				54070	143	144	1	<0.03	0.10
				54071	144	145	1	<0.03	0.10
120.0		117.70 - 131.68 GRITTY PSAMMITE: Gritty psammite with laminations at 75 deg. of chlorite and biotite altered phyllite, locally kinked or sigmoidal with weak rusty laminations. Hairline rusty fractures and rare quartz veinlets at all orientations.							
		131.68 - 148.13 QUARTZOFELDSPATHIC & MICACEOUS PSAMMITE: Locally rusty and contorted, faulted and broken chloritic phyllite with psammite and gritty psammite interbeds. Rusted out disseminated cubic pyrite pits up to 2 mm, trace to 1%. 135.94 - 136.9 rusty, sandy fault, poor recovery. 138.0 - 138.07 rusty, sandy fault, poor recovery.							
130.0									
140.0									

SCALE (meters)	Lithology Structure 0 90 T.C.A.	Magnetic Susceptibility 0 1.0	LITHOLOGIC DESCRIPTION	Core Recovery	SAMPLE DATA																								
					<table border="1" style="width:100%; border-collapse: collapse;"> <thead> <tr> <th style="width:15%;">Sample No.</th> <th style="width:15%;">From (m)</th> <th style="width:15%;">To (m)</th> <th style="width:15%;">Interval (m)</th> <th style="width:15%;">Au (gpt)</th> <th style="width:15%;">Ag (gpt)</th> </tr> </thead> <tbody> <tr> <td>54072</td> <td>145</td> <td>146</td> <td>1</td> <td><0.03</td> <td>0.10</td> </tr> <tr> <td>54073</td> <td>146</td> <td>147</td> <td>1</td> <td><0.03</td> <td>0.10</td> </tr> <tr> <td>54074</td> <td>147</td> <td>148.13</td> <td>1.13</td> <td><0.03</td> <td>0.10</td> </tr> </tbody> </table>	Sample No.	From (m)	To (m)	Interval (m)	Au (gpt)	Ag (gpt)	54072	145	146	1	<0.03	0.10	54073	146	147	1	<0.03	0.10	54074	147	148.13	1.13	<0.03	0.10
Sample No.	From (m)	To (m)	Interval (m)	Au (gpt)	Ag (gpt)																								
54072	145	146	1	<0.03	0.10																								
54073	146	147	1	<0.03	0.10																								
54074	147	148.13	1.13	<0.03	0.10																								



Appendix III

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 136
Sample Type: Core
Project: CWG-7518-YT
Shipment #: 7
Submitted by: Kel Sax

Values in ppm unless otherwise reported

Table with 30 columns representing elements (Ag to Zn) and 30 rows representing sample IDs (1 to 30). Each cell contains a numerical value representing the concentration of that element in the sample.

Et #.	Tag #	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppb	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm
31	7R53833	0.2	1.31	4.2	50.5	0.72	0.35	0.05	12.9	64.0	37.55	3.36	5.6	20	0.31	21.0	0.68	662	0.52	0.032	28.4	321.0	44.30	0.10	0.10	1.5	0.9	45.0	0.06	16.1	0.001	0.12	2.2	10	<0.1	95.5	
32	7R53834	0.2	0.72	5.1	47.5	0.64	0.34	0.05	12.1	75.5	32.08	3.12	5.0	30	0.28	30.5	0.64	591	0.43	0.027	26.6	304.0	41.37	0.14	0.14	1.4	1.2	42.0	0.06	17.7	0.005	0.12	2.2	6	<0.1	89.1	
33	7R53835	0.1	0.53	5.2	54.5	0.64	0.22	0.04	11.5	70.5	27.17	3.02	5.0	40	0.30	35.5	0.52	415	0.34	0.026	22.0	286.0	40.60	0.06	0.06	1.4	1.3	30.5	0.08	19.6	0.005	0.12	2.0	4	<0.1	95.9	
34	7R53836	0.1	0.59	7.3	55.0	0.64	0.32	0.05	13.8	53.5	38.90	3.78	4.0	40	0.34	23.5	0.69	845	0.54	0.031	24.8	417.0	42.84	0.24	0.14	1.7	1.1	40.5	0.08	19.2	0.005	0.14	2.3	6	<0.1	110.9	
35	7R53837	0.1	0.58	5.4	55.0	0.42	0.52	0.06	9.4	74.5	21.95	2.45	3.5	25	0.28	17.5	0.45	657	0.39	0.031	15.5	278.0	38.08	0.14	0.08	1.2	0.7	64.0	0.06	14.4	0.001	0.12	1.9	4	<0.1	72.3	
36	7R53838	0.1	0.35	3.2	55.5	0.34	0.37	0.05	6.2	96.5	16.90	1.72	2.4	30	0.19	13.5	0.29	475	0.46	0.028	11.3	120.0	36.29	0.10	0.10	0.7	0.6	50.5	0.04	10.5	0.001	0.08	1.2	2	<0.1	49.3	
37	7R53839	0.1	0.63	6.5	64.0	0.86	0.18	0.08	13.3	55.5	45.07	3.61	6.0	45	0.38	39.0	0.57	550	0.66	0.026	27.0	353.0	58.16	0.24	0.12	1.6	1.6	29.0	0.10	22.7	0.001	0.16	2.5	6	<0.1	107.7	
38	7R53840	0.1	0.52	6.2	57.0	0.58	0.47	0.06	11.0	70.0	31.35	2.81	5.0	45	0.34	34.5	0.46	607	0.50	0.025	19.7	236.0	45.28	0.14	0.10	1.3	1.3	49.0	0.08	19.9	0.001	0.14	2.2	4	<0.1	78.2	
39	7R53841	0.1	0.38	2.6	45.5	0.18	0.45	0.04	4.1	128.5	10.88	1.17	2.2	20	0.19	12.5	0.19	316	0.47	0.022	7.8	83.0	32.39	0.06	0.08	0.6	0.5	42.5	0.04	9.3	0.001	0.08	1.0	<2	<0.1	29.7	
40	7R53842	0.1	0.41	3.3	50.5	0.22	0.41	0.03	4.4	138.0	11.29	1.22	2.4	20	0.22	13.5	0.19	328	0.44	0.025	8.4	91.0	34.46	0.06	0.08	0.6	0.5	43.0	0.04	10.2	0.001	0.08	1.2	<2	<0.1	29.3	
41	7R53843	0.1	0.37	3.2	48.5	0.20	0.34	0.02	4.5	107.5	11.06	1.19	2.3	15	0.21	13.0	0.16	340	0.43	0.024	8.0	107.0	31.72	0.06	0.08	0.5	0.5	36.5	0.04	10.4	0.002	0.08	1.2	<2	<0.1	28.9	
42	7R53844	0.1	0.36	2.8	46.0	0.16	0.28	0.04	4.1	134.5	10.34	1.02	2.5	15	0.21	14.0	0.14	281	0.56	0.029	7.7	85.0	30.76	0.06	0.08	0.5	0.5	30.5	0.04	9.4	0.004	0.10	1.0	2	<0.1	27.7	
43	7R53845	0.1	0.49	5.0	50.5	0.46	0.17	0.07	10.3	97.5	28.73	3.02	3.4	50	0.30	20.5	0.40	541	0.50	0.022	20.2	323.0	46.80	0.22	0.16	1.4	1.0	20.0	0.08	19.1	0.001	0.10	1.6	4	<0.1	77.9	
44	7R53846	0.2	0.44	2.9	65.5	0.62	0.05	0.02	8.7	47.0	19.82	3.32	4.4	95	0.33	27.5	0.09	321	1.34	0.024	14.1	197.0	57.36	0.18	0.56	1.2	1.2	27.0	0.12	18.1	0.002	0.18	2.2	6	<0.1	61.4	
45	7R53847	0.1	0.51	4.4	50.0	0.22	0.05	0.06	6.3	114.5	19.53	1.82	3.5	40	0.22	20.5	0.08	393	0.61	0.025	12.2	118.0	30.89	0.06	0.14	0.8	0.8	12.0	0.04	13.0	0.001	0.10	2.1	2	<0.1	45.5	
46	7R53848	0.1	0.37	2.6	49.5	0.28	0.03	0.07	6.7	75.0	23.14	2.23	2.5	55	0.26	15.0	0.06	145	0.50	0.022	12.2	129.0	34.21	0.28	0.34	1.0	0.7	7.0	0.06	12.9	0.001	0.12	1.6	2	<0.1	43.8	
47	7R53849	0.1	0.28	0.9	31.0	0.16	0.26	0.05	5.1	87.5	9.29	1.07	1.2	30	0.15	6.0	0.10	672	0.43	0.024	9.7	72.0	28.29	0.32	0.18	0.6	0.3	17.0	0.04	7.6	0.005	0.06	1.2	<2	<0.1	26.0	
48	7R53850	0.1	0.18	2.0	30.5	0.16	0.03	<0.01	1.9	111.5	6.20	1.22	1.5	20	0.14	9.5	0.02	89	0.36	0.021	5.1	82.0	30.81	0.04	0.18	0.6	0.4	9.0	0.04	8.7	0.005	0.06	0.8	<2	<0.1	16.5	
49	7R53851	0.1	0.19	1.6	28.0	0.16	0.03	0.03	2.5	65.5	8.64	0.94	1.5	15	0.13	10.0	0.02	207	0.30	0.016	5.7	116.0	29.45	0.06	0.10	0.4	0.4	9.0	0.02	7.8	0.001	0.04	0.9	<2	<0.1	18.3	
50	7R53852	0.1	0.36	4.0	42.5	0.20	0.06	0.06	6.6	121.5	17.79	1.58	3.2	20	0.23	20.0	0.09	620	0.47	0.020	12.6	155.0	30.59	0.10	0.08	0.7	0.9	6.0	0.04	12.1	0.001	0.08	1.2	<2	<0.1	34.0	
51	7R53853	0.1	0.35	4.2	41.0	0.22	0.07	0.04	6.9	107.5	16.25	1.58	3.3	20	0.21	21.0	0.12	707	0.48	0.023	12.1	151.0	33.09	0.08	0.08	0.8	0.9	6.5	0.04	12.4	0.002	0.08	1.4	2	<0.1	40.3	
52	7R53854	0.1	0.38	3.1	41.0	0.20	0.05	0.04	6.9	125.5	12.53	1.35	2.3	20	0.19	13.0	0.06	721	0.50	0.024	13.3	116.0	32.02	0.06	0.10	0.7	0.6	5.0	0.04	10.3	0.001	0.06	1.3	<2	<0.1	34.0	
53	7R53855	0.1	0.36	4.4	41.0	0.22	0.03	0.02	5.9	144.5	18.96	1.99	2.8	20	0.21	18.0	0.04	188	0.57	0.021	11.6	174.0	30.41	0.02	0.18	0.7	0.7	5.5	0.04	11.7	0.001	0.08	1.4	<2	<0.1	39.9	
54	7R53856	0.1	0.33	2.2	38.0	0.18	0.03	0.05	5.8	166.0	11.04	1.17	2.0	15	0.16	11.0	0.03	341	0.46	0.021	8.9	98.0	29.95	<0.02	0.08	0.5	0.5	6.0	0.02	8.4	0.001	0.06	1.1	<2	<0.1	27.2	
55	7R53857	0.1	0.33	3.4	35.5	0.18	0.03	0.01	2.2	132.0	10.39	1.58	2.2	15	0.16	14.5	0.03	81	0.39	0.019	6.6	105.0	30.61	<0.02	0.10	0.5	0.6	3.5	0.04	10.5	0.001	0.06	1.1	<2	<0.1	25.9	
56	7R53858	0.1	0.24	3.2	24.5	0.14	0.02	0.01	1.0	154.0	10.44	0.95	1.9	15	0.13	12.5	0.02	36	0.39	0.019	5.3	80.0	30.03	<0.02	0.08	0.4	0.5	3.0	0.02	7.8	0.005	0.04	0.8	<2	<0.1	21.7	
57	7R53859	0.1	0.32	3.9	37.0	0.32	0.03	0.02	2.4	115.0	22.83	1.87	2.9	45	0.21	19.5	0.02	43	0.45	0.022	7.9	200.0	35.90	0.04	0.20	1.0	0.8	10.5	0.06	16.1	0.005	0.08	1.3	<2	<0.1	34.6	
58	7R53860	0.1	0.47	4.9	44.5	0.54	0.20	0.11	12.7	98.5	39.69	3.07	3.2	65	0.25	20.0	0.10	391	0.53	0.023	27.3	984.0	45.83	0.26	0.28	1.7	1.3	43.5	0.08	18.3	0.005	0.08	2.9	4	<0.1	99.5	
59	7R53861	0.1	0.34	3.2	44.0	0.40	0.03	0.04	8.2	99.5	46.90	4.14	3.6	35	0.21	27.0	0.03	166	0.55	0.023	20.4	280.0	41.40	0.06	0.36	1.6	1.2	13.5	0.08	20.6	0.005	0.06	2.1	2	<0.1	74.2	
60	7R53862	0.1	0.33	3.3	37.0	0.24	0.03	0.03	7.3	123.5	27.07	2.68	3.2	25	0.17	23.5	0.03	277	0.48	0.022	18.4	241.0	34.03	<0.02	0.26	1.3	0.9	6.0	0.06	14.8	0.005	0.06	1.9	<2	<0.1	55.7	
61	7R53863	0.1	0.38	3.6	46.0	0.34	0.05	0.06	12.7	101.5	21.02	2.30	4.3	40	0.21	31.5	0.04	398	0.36	0.021	19.4	204.0	35.44	<0.02	0.22	1.3	1.4	7.0	0.06	16.3	0.005	0.08	1.6	<2	<0.1	65.7	
62	7R53864	0.4	0.51	2.7	56.0	0.40	4.04	0.07	11.6	89.0	27.78	2.86	3.6	50	0.28	27.0	0.41	482	0.49	0.025	21.4	272.0	44.87	0.54	0.12	1.7	1.2	188.0	0.06	20.8	0.001	0.08	1.8	2	<0.1	64.5	
63	7R53865	0.2	0.29	1.5	33.0	0.12	7.18	0.04	5.9	94.5	10.77	1.43	2.2	30	0.16	15.5	0.29	305	0.32	0.026	9.9	147.0	22.44	0.40	0.06	1.3	0.8	304.5	0.04	11.2	0.005	0.06	1.1	<2	<0.1	35.7	
64	7R53866	0.1	0.34	1.7	41.0	0.18	>10	0.04	6.4	78.0	14.12	1.72	1.9	30	0.17	14.0	0.28	562	0.43	0.025	11.6	424.0	26.42	0.30	0.10	1.8	0.9	341.0	0.06	11.7	0.005	0.04	1.3	<2	<0.1	35.7	
65	7R53867	0.1	0.44	1.5	50.0	0.34	4.30	0.05	11.2	101.0	23.01	2.37	2.7	45	0.24	18.5	0.45	414	0.45	0.027	19.8	176.0	36.84	0.48	0.16	1.4	0.9	207.0	0.04	16.1	0.005	0.08	1.6	<2	<0.1	58.2	
66	7R53868	0.1	0.44	1.2	55.0	0.54	2.03	0.07	11.8	83.5	32.71	2.98	3.0	65	0.26	21.0	0.54	471	0.49	0.027	22.1	200.0	46.10	0.60	0.16	1.3	0.9	89.5	0.06	21.2	0.005	0.08	2.2	<2	<0.1	70.1	
67	7R53869	0.1	0.33	4.2	41.0																																

76	7R53878	0.2	0.39	6.1	33.0	0.36	0.76	0.05	9.6	131.0	23.05	2.79	2.7	50	0.17	18.0	0.41	490	0.59	0.020	18.4	122.0	28.97	0.44	0.34	1.9	0.9	65.5	0.06	16.0	0.005	0.08	1.2	4	<0.1	62.2
77	7R53879	0.1	0.35	4.5	44.0	0.36	0.61	0.05	8.0	109.5	21.11	2.28	3.2	35	0.21	23.0	0.42	459	0.48	0.021	15.0	128.0	28.40	0.18	0.10	1.0	0.9	54.0	0.06	15.0	0.005	0.06	1.0	<2	<0.1	59.6
78	7R53880	0.1	0.45	3.3	53.0	0.58	0.51	0.08	11.8	111.0	36.04	2.98	3.7	40	0.26	23.0	0.43	606	0.59	0.022	23.2	152.0	45.54	0.62	0.14	1.2	0.9	50.5	0.06	19.9	0.001	0.12	1.9	4	<0.1	78.2
79	7R53881	0.3	0.53	2.5	48.5	0.50	0.52	0.06	12.3	90.5	30.64	3.14	4.4	20	0.27	29.5	0.44	540	0.57	0.024	24.1	159.0	37.00	0.78	0.10	1.0	1.0	47.0	0.08	24.3	0.001	0.14	3.1	2	<0.1	86.5
80	7R53882	0.1	0.62	6.0	55.0	0.58	0.48	0.09	13.5	104.5	37.07	3.38	5.4	15	0.28	36.0	0.54	720	0.58	0.025	24.9	195.0	42.36	0.32	0.10	1.2	1.3	54.0	0.08	24.3	0.001	0.10	3.0	4	<0.1	85.6
81	7R53883	0.1	0.48	3.8	47.0	0.46	0.68	0.11	9.6	85.5	27.50	2.89	4.0	15	0.23	25.5	0.53	845	0.45	0.022	17.6	147.0	38.38	0.22	0.08	1.0	1.0	71.0	0.06	19.6	0.005	0.10	2.1	2	<0.1	71.7
82	7R53884	0.1	0.52	7.3	50.0	0.60	0.79	0.16	15.4	90.5	35.52	3.35	4.6	20	0.26	32.5	0.56	883	0.57	0.024	24.1	171.0	41.67	0.56	0.14	1.3	1.2	79.0	0.08	24.3	0.001	0.08	2.6	4	<0.1	84.6
83	7R53885	0.1	0.57	2.1	19.5	0.58	0.28	0.10	14.7	80.5	37.43	3.86	3.0	20	0.25	14.0	0.41	439	0.62	0.026	26.5	278.0	37.25	1.62	0.26	1.1	0.8	32.0	0.08	17.6	0.001	0.14	2.9	4	<0.1	86.0
84	7R53886	0.1	0.62	1.8	16.5	0.68	0.34	0.13	14.7	71.0	44.96	4.00	2.7	20	0.26	11.0	0.41	511	0.61	0.024	29.2	385.0	44.77	1.80	0.22	1.0	0.8	38.0	0.08	16.4	0.001	0.12	2.4	4	<0.1	92.3
85	7R53887	0.1	0.54	1.7	27.5	0.52	0.35	0.13	13.4	90.0	40.88	3.43	2.8	20	0.27	13.0	0.45	568	0.62	0.023	27.2	154.0	46.45	1.04	0.20	1.1	0.6	38.5	0.06	14.5	0.001	0.12	2.3	4	<0.1	91.5
86	7R53888	0.1	0.53	3.6	49.0	0.58	0.58	0.11	12.3	72.0	35.78	3.43	3.9	30	0.26	25.5	0.54	555	0.55	0.021	23.4	204.0	40.39	0.76	0.12	1.2	1.0	58.0	0.08	20.2	0.005	0.10	2.1	4	<0.1	83.2
87	7R53889	0.1	0.49	3.5	50.5	0.56	0.54	0.11	11.4	80.5	32.78	3.12	4.2	30	0.26	27.5	0.43	584	0.54	0.022	23.1	163.0	45.84	0.60	0.12	1.1	1.1	58.0	0.08	22.5	0.005	0.10	2.0	2	<0.1	79.5
88	7R53890	0.1	0.47	3.5	45.5	0.38	0.76	0.06	8.0	101.0	23.72	2.40	3.3	25	0.21	21.5	0.39	524	0.48	0.023	16.5	115.0	33.63	0.36	0.12	0.9	0.9	72.5	0.04	17.2	0.005	0.08	1.9	2	<0.1	56.1
89	7R53891	0.1	0.39	4.2	51.0	0.44	0.68	0.07	10.7	99.5	25.27	2.60	4.0	50	0.24	27.5	0.40	455	0.54	0.021	18.5	182.0	40.74	0.46	0.18	1.1	1.1	60.5	0.06	19.4	0.001	0.08	1.3	2	<0.1	72.0
90	7R53892	0.1	0.45	4.0	57.0	0.66	0.65	0.10	12.2	99.5	35.98	3.11	4.7	40	0.27	37.0	0.47	455	0.55	0.027	22.9	195.0	54.34	0.48	0.14	1.3	1.3	67.0	0.08	24.8	0.005	0.10	2.2	2	<0.1	86.9
91	7R53893	0.1	0.57	6.7	56.5	0.52	0.69	0.08	13.0	98.0	34.65	3.28	4.4	30	0.25	33.0	0.52	607	0.53	0.027	23.0	188.0	46.73	0.50	0.14	1.2	1.2	66.5	0.08	23.3	0.005	0.10	2.1	4	<0.1	84.5
92	7R53894	0.2	0.47	3.2	32.5	0.58	1.07	0.07	13.6	84.5	35.74	3.23	4.0	45	0.25	32.0	0.52	526	0.60	0.025	25.0	189.0	42.93	0.86	0.24	1.1	1.2	82.0	0.08	23.6	0.005	0.08	1.9	2	<0.1	74.6
93	7R53895	0.1	0.27	3.0	32.0	0.14	>10	0.03	5.1	64.5	10.77	1.61	1.7	20	0.13	13.5	0.32	427	0.39	0.025	8.6	302.0	22.89	0.34	0.10	1.1	0.6	741.5	0.06	10.3	0.005	0.04	1.5	<2	<0.1	34.2
94	7R53896	0.1	0.39	3.5	47.5	0.40	9.62	0.07	10.1	64.5	25.82	2.75	1.7	40	0.20	10.0	0.45	476	0.54	0.026	19.2	256.0	33.18	0.86	0.22	1.7	0.9	465.5	0.08	14.8	0.005	0.06	1.6	<2	<0.1	54.8
95	7R53897	0.1	0.30	6.9	47.5	0.32	7.69	0.02	7.4	76.5	15.89	2.06	1.8	20	0.19	12.0	0.46	373	0.44	0.025	15.2	286.0	33.39	0.12	0.08	1.3	0.6	391.5	0.06	11.1	0.005	0.06	0.9	2	<0.1	46.1
96	7R53898	0.1	0.43	3.8	53.0	0.52	0.92	0.05	12.5	67.0	37.62	3.47	2.5	40	0.22	15.5	0.63	585	0.64	0.026	25.5	233.0	33.76	0.46	0.12	1.4	0.8	72.0	0.06	17.2	0.005	0.06	1.3	4	<0.1	79.2
97	7R53899	0.1	0.38	1.4	33.5	0.72	2.89	0.14	13.7	73.0	39.61	3.74	2.4	55	0.23	18.0	0.73	787	0.90	0.025	26.8	354.0	44.48	1.36	0.20	1.7	1.0	176.0	0.08	21.4	0.005	0.06	1.6	<2	<0.1	72.4
98	7R53900	0.1	0.55	5.6	51.5	0.40	1.78	0.06	15.3	72.0	35.56	3.59	3.5	45	0.21	25.5	0.90	795	0.66	0.028	25.9	345.0	36.77	0.44	0.14	1.6	1.1	147.5	0.08	19.2	0.005	0.08	1.6	4	<0.1	77.9
99	7R53901	0.1	0.65	4.4	50.0	0.42	2.81	0.13	12.3	43.5	32.81	3.58	3.9	35	0.21	31.0	1.02	944	0.64	0.028	24.9	343.0	36.05	0.44	0.10	1.9	1.3	205.0	0.06	20.4	0.005	0.06	1.3	4	<0.1	70.5
100	7R53902	0.1	0.45	4.7	38.5	0.42	3.35	0.13	16.6	25.5	36.58	3.57	3.3	35	0.16	29.5	1.09	965	0.64	0.026	25.2	335.0	37.21	0.66	0.12	1.7	1.3	240.5	0.08	20.1	0.005	0.06	1.3	<2	<0.1	50.0
101	7R53903	0.1	0.21	1.2	33.0	0.28	7.66	0.17	9.4	91.0	24.79	2.22	1.6	25	0.12	12.0	0.44	960	0.72	0.025	12.8	129.0	36.69	0.84	0.20	1.4	0.9	354.5	0.06	9.5	0.005	0.04	0.8	<2	<0.1	34.8
102	7R53904	0.1	0.47	1.4	39.5	0.40	5.13	0.33	19.4	30.5	38.64	3.95	2.4	40	0.17	19.5	1.14	1289	0.79	0.025	30.9	747.0	41.06	1.30	0.30	2.2	1.3	323.5	0.10	16.3	0.005	0.04	1.2	<2	<0.1	61.2
103	7R53905	0.1	0.44	1.4	34.5	0.40	4.30	0.36	18.0	36.5	34.68	3.63	2.4	40	0.14	19.5	1.01	1213	0.70	0.025	26.1	286.0	48.03	1.10	0.22	1.9	1.1	252.5	0.08	14.9	0.005	0.04	0.9	<2	<0.1	61.3
104	7R53906	0.2	0.45	2.1	45.5	0.48	3.67	0.17	16.7	38.0	46.73	3.46	3.2	30	0.19	28.5	0.96	1021	0.68	0.024	25.5	312.0	41.22	0.88	0.18	1.9	1.3	228.0	0.10	17.8	0.005	0.06	1.1	<2	<0.1	46.8
105	7R53907	0.1	0.55	5.7	47.0	0.32	2.80	0.06	11.4	30.0	28.06	3.36	3.7	20	0.19	33.0	0.97	965	0.58	0.024	22.8	317.0	31.44	0.22	0.10	1.9	1.2	216.0	0.08	19.6	0.005	0.06	1.5	4	<0.1	68.7
106	7R53908	0.1	0.77	4.3	56.5	0.56	2.72	0.10	14.0	60.5	38.12	3.70	4.1	20	0.22	29.0	1.03	915	0.69	0.026	25.4	311.0	47.95	0.38	0.12	1.8	1.2	214.5	0.08	18.7	0.001	0.08	2.2	4	<0.1	71.1
107	7R53909	0.1	0.70	1.9	51.5	0.50	1.85	0.09	15.1	24.5	42.35	4.13	3.4	30	0.17	17.0	0.91	931	0.73	0.026	30.7	440.0	48.22	0.42	0.12	1.9	0.9	143.5	0.08	18.1	0.005	0.06	1.7	6	<0.1	95.0
108	7R53910	0.1	0.67	1.0	45.5	0.58	2.64	0.15	14.6	41.5	41.71	4.01	2.8	40	0.24	17.0	0.94	896	0.84	0.028	28.1	419.0	46.47	0.74	0.12	2.0	0.9	194.0	0.06	18.7	0.005	0.08	1.8	4	<0.1	78.9
109	7R53911	0.1	0.30	1.2	36.0	0.48	5.44	0.12	10.0	36.0	31.54	3.07	2.2	30	0.15	20.0	0.82	810	0.41	0.027	19.0	367.0	44.30	0.64	0.14	1.8	1.0	257.5	0.06	17.6	0.005	0.08	1.3	<2	<0.1	59.9
110	7R53912	0.1	0.34	5.1	46.0	0.52	1.37	0.13	15.3	41.5	46.84	3.57	3.8	30	0.19	29.5	0.64	685	0.74	0.022	28.4	307.0	42.96	0.68	0.12	1.4	1.2	119.5	0.06	22.3	0.005	0.08	1.3	4	<0.1	81.0
111	7R53913	0.1	0.49	7.6	50.0	0.46	0.74	0.03	11.2	38.0	28.75	3.17	5.3	10	0.17	41.0	0.54	521	0.59	0.024	22.0	241.0	42.12	0.06	0.06	1.3	1.3	68.5	0.06	22.1	0.005	0.08	1.3	4	<0.1	78.8
112	7R53914	0.2	0.70	5.0	55.0	0.50	0.59	0.07	12.4	45.0	35.79	3.35	5.0	25	0.22	37.5	0.58	405	0.68	0.027	26.4	349.0	45.80	0.28	0.08	1.4	1.3	49.5	0.06	22.5	0.005	0.10	1.6	4		

123	7R53925	0.1	0.52	6.7	49.0	0.34	0.88	0.06	8.1	103.5	21.52	2.41	3.9	15	0.19	28.5	0.42	630	0.48	0.024	14.9	139.0	40.70	0.20	0.06	1.0	0.9	81.5	0.04	19.6	0.001	0.08	2.4	2	<0.1	63.7
124	7R53926	0.1	0.73	4.7	53.0	0.60	0.46	0.09	11.8	66.0	38.24	3.61	4.3	25	0.23	27.5	0.49	478	0.56	0.025	25.4	202.0	51.00	0.44	0.06	1.5	1.0	45.0	0.06	25.9	0.001	0.08	3.5	4	<0.1	94.2
125	7R53927	0.2	0.84	6.1	47.5	0.74	0.35	0.07	13.0	78.5	41.34	3.36	4.8	25	0.21	31.5	0.43	394	0.51	0.025	24.2	191.0	51.08	0.60	0.08	1.1	1.0	38.5	0.06	26.7	0.001	0.08	2.9	4	<0.1	85.8
126	7R53928	0.1	0.74	7.7	49.0	0.50	0.71	0.07	11.7	84.0	26.64	3.13	5.2	15	0.22	39.0	0.49	774	0.55	0.024	19.2	194.0	42.50	0.30	0.06	1.2	1.2	73.0	0.06	27.1	0.001	0.08	3.5	4	<0.1	83.6
127	7R53929	0.1	0.64	3.5	31.0	0.70	0.39	0.11	13.9	73.5	40.41	3.54	5.1	40	0.25	45.0	0.38	454	0.61	0.026	25.5	187.0	51.56	0.92	0.08	1.3	1.3	43.5	0.08	33.9	0.001	0.10	2.6	4	<0.1	92.8
128	7R53930	0.2	0.68	2.7	23.5	0.80	0.28	0.08	16.1	57.0	42.74	3.75	4.7	55	0.24	39.5	0.40	330	0.58	0.024	27.5	185.0	62.03	1.14	0.12	1.2	1.1	34.0	0.08	32.7	0.001	0.10	2.8	2	<0.1	91.8
129	7R53931	0.1	0.43	2.4	34.0	0.22	0.67	0.05	5.6	125.5	16.58	1.89	2.4	25	0.14	18.0	0.29	573	0.59	0.028	11.4	77.0	33.87	0.34	0.08	0.6	0.6	68.5	0.04	14.9	0.005	0.06	2.2	<2	<0.1	41.4
130	7R53932	0.1	0.74	6.6	55.0	1.04	1.06	0.11	15.2	74.0	54.75	3.86	5.3	55	0.27	45.5	0.46	485	0.91	0.028	25.5	#####	53.38	0.60	0.20	1.7	2.1	126.0	0.08	33.8	0.001	0.10	3.7	4	<0.1	95.6
131	7R53933	0.1	0.50	3.9	42.0	0.34	0.79	0.05	5.7	121.0	16.74	1.86	3.0	20	0.16	24.0	0.32	490	0.48	0.025	11.9	247.0	41.51	0.10	0.10	0.7	0.8	80.0	0.02	15.4	0.001	0.08	2.0	<2	<0.1	50.2
132	7R53934	0.1	0.47	3.0	43.0	0.62	0.36	0.10	10.6	76.0	33.29	2.95	4.1	50	0.23	36.5	0.33	333	0.55	0.023	21.0	145.0	54.55	0.68	0.20	1.0	1.1	39.0	0.06	26.2	0.005	0.10	2.7	<2	<0.1	74.1
133	7R53935	0.1	0.43	1.7	53.5	0.52	0.02	0.15	7.9	84.5	40.40	2.05	3.0	30	0.22	22.0	0.03	123	0.40	0.024	25.1	190.0	41.67	<0.02	0.06	0.9	0.8	7.0	0.04	19.9	0.005	0.08	3.2	<2	<0.1	77.1
134	7R53936	0.1	0.46	0.9	49.5	0.46	0.02	0.15	10.7	54.0	47.72	2.79	3.1	15	0.19	21.5	0.04	372	0.31	0.024	27.8	178.0	39.57	<0.02	0.04	0.9	0.8	7.5	0.04	22.8	0.005	0.10	2.5	2	<0.1	76.5
135	7R53937	0.1	0.33	1.5	49.0	0.32	0.01	0.04	5.5	123.0	45.06	1.71	2.8	20	0.21	23.5	0.02	75	0.61	0.024	17.0	111.0	34.96	<0.02	0.08	0.6	0.8	4.0	0.04	18.3	0.005	0.06	1.5	<2	<0.1	42.3
136	7R53938	0.2	0.18	0.6	25.5	0.16	0.03	0.02	2.9	150.0	22.55	0.94	1.5	10	0.12	11.5	0.01	65	0.45	0.022	9.2	124.0	39.32	<0.02	0.06	0.3	0.4	6.5	0.02	8.6	0.005	0.06	0.7	<2	<0.1	24.9

QC DATA:

Repeat:

1	7R53803	0.2	0.38	3.2	52.5	0.22	0.02	0.04	1.7	91.0	45.68	2.24	3.3	190	0.20	21.5	0.03	42	0.87	0.022	9.1	209.0	25.45	0.02	0.36	1.0	1.4	7.5	0.06	9.1	0.005	0.06	1.0	2	<0.1	21.7
10	7R53812	0.1	0.62	5.6	87.0	0.18	0.06	0.07	12.4	83.5	34.03	3.50	5.6	65	0.20	37.0	0.16	556	0.36	0.029	43.4	452.0	25.15	<0.02	0.16	2.4	2.0	7.0	0.04	12.1	0.001	0.12	0.8	8	<0.1	98.8
19	7R53821	0.1	1.94	15.9	56.1	0.16	0.18	0.28	19.5	107.7	47.79	4.52	8.3	15	0.24	25.0	1.22	1061	0.61	0.034	58.4	660.5	28.77	0.11	0.09	2.2	1.1	16.1	0.04	13.2	0.002	0.09	1.4	24	<0.1	108.3
36	7R53838	0.1	0.37	3.3	57.0	0.36	0.39	0.05	6.3	97.5	16.87	1.81	2.9	30	0.21	16.0	0.31	489	0.45	0.029	11.6	131.0	39.31	0.12	0.08	0.8	0.6	52.5	0.04	12.2	0.001	0.10	1.3	4	<0.1	49.5
45	7R53847	0.2	0.53	3.9	50.5	0.20	0.05	0.06	5.8	116.5	19.40	1.80	3.5	35	0.22	21.0	0.08	388	0.59	0.026	12.2	116.0	30.11	0.06	0.14	0.8	0.8	12.0	0.06	12.7	0.002	0.10	2.1	2	<0.1	43.2
54	7R53856	0.1	0.34	2.3	38.5	0.16	0.03	0.05	5.7	170.0	11.03	1.15	2.0	15	0.16	12.0	0.03	335	0.48	0.020	8.8	101.0	29.69	<0.02	0.08	0.5	0.5	6.0	0.02	8.1	0.001	0.06	1.1	<2	<0.1	27.0
71	7R53873	0.1	0.39	3.7	44.5	0.30	0.06	0.04	9.7	86.0	20.32	2.43	3.5	35	0.20	24.5	0.05	284	0.25	0.020	15.2	150.0	31.01	<0.02	0.16	0.8	1.0	10.0	0.04	16.5	0.005	0.08	1.1	<2	<0.1	59.4
80	7R53882	0.1	0.59	5.5	53.0	0.58	0.46	0.10	13.1	99.0	36.40	3.34	4.9	15	0.26	33.5	0.52	701	0.54	0.024	24.2	186.0	39.99	0.32	0.10	1.1	1.3	52.0	0.06	24.0	0.001	0.10	2.9	4	<0.1	82.7
89	7R53891	0.1	0.37	3.7	49.5	0.44	0.66	0.07	10.1	96.5	23.81	2.55	3.5	50	0.22	25.0	0.37	439	0.51	0.022	17.7	175.0	40.13	0.42	0.18	1.0	0.9	58.0	0.04	17.7	0.005	0.08	1.2	2	<0.1	69.5
106	7R53908	0.1	0.76	3.9	54.5	0.54	2.66	0.11	13.1	58.5	36.71	3.64	4.1	20	0.22	29.0	0.99	8976	0.67	0.026	24.1	300.0	47.80	0.36	0.12	1.9	1.1	204.5	0.08	19.0	0.001	0.08	2.1	4	<0.1	69.5
115	7R53917	0.1	0.12	4.9	29.0	0.08	>10	0.03	3.8	30.0	11.91	0.99	0.9	5	0.07	10.0	0.40	275	0.26	0.032	5.6	320.0	24.03	0.30	0.22	1.5	0.5	1289.0	0.08	6.8	0.005	0.02	0.9	<2	<0.1	17.2
124	7R53926	0.1	0.74	7.9	54.5	0.62	0.45	0.09	14.9	67.0	37.18	3.64	4.6	25	0.24	30.0	0.49	476	0.62	0.025	25.7	203.0	52.01	0.44	0.06	1.3	1.1	45.0	0.06	27.5	0.001	0.10	3.6	4	<0.1	93.0

Resplit:

1	7R53803	0.1	0.37	3.1	53.0	0.22	0.02	0.04	1.8	88.0	45.05	2.25	3.2	185	0.20	21.5	0.03	42	0.88	0.022	8.7	196.0	27.12	<0.02	0.36	0.9	1.3	7.0	0.06	10.2	0.005	0.06	1.0	2	<0.1	21.4
36	7R53838	0.1	0.35	3.4	57.0	0.36	0.37	0.04	6.2	99.5	16.31	1.76	2.6	30	0.20	15.5	0.29	482	0.41	0.028	11.1	128.0	44.87	0.10	0.10	0.8	0.6	53.0	0.06	13.3	0.001	0.08	1.3	2	<0.1	51.2
71	7R53873	0.1	0.37	3.3	42.5	0.30	0.06	0.04	8.9	84.5	18.86	2.37	3.1	35	0.19	23.0	0.04	276	0.24	0.022	13.7	146.0	32.70	<0.02	0.18	0.8	0.8	9.5	0.04	15.2	0.005	0.06	1.1	<2	<0.1	56.1
106	7R53908	0.1	0.73	3.3	51.5	0.52	2.54	0.08	12.4	54.0	35.59	3.51	3.6	20	0.20	27.5	0.96	888	0.61	0.027	22.3	286.0	50.96	0.35	0.10	1.6	1.0	197.0	0.06	21.9	0.005	0.08	2.1	4	<0.1	66.7

Standard:

PB113A		10.9	0.27	59.6	38.5	1.10	1.60	43.36	1.7	5.0	2334.00	1.06	1.3	70	0.15	2.5	0.11	1563	68.20	0.029	1.3	90.0	5571.00	1.04	9.58	0.4	0.5	102.0	0.28	3.2	0.005	0.08	0.4	6	<0.1	7024.0
PB113A		11.3	0.27	61.7	35.5	1.10	1.58	43.65	1.6	4.5	2264.00	1.05	1.3	70	0.16	2.5	0.10	1551	68.19	0.029	1.3	103.0	5494.00	1.06	9.82	0.4	0.5	103.5	0.28	4.1	0.005	0.08	0.3	6	<0.1	6925.0
PB113A		11.4	0.26	62.0	36.5	1.12	1.65	45.41	1.6	4.5	2276.00	1.03	1.2	75	0.14	2.5	0.10	1528	70.79	0.028	1.2	85.0	5498.00	1.04	10.56	0.4	0.4	105.0	0.28	3.7	0.004	0.08	0.4	6	<0.1	6960.0
PB113A		11.1	0.26	61.2	37.0	1.13	1.60	47.90	1.6	4.5	2325.00	1.05	1.3	75	0.15	3.0	0.10	1556	71.48	0.030	1.2	95.0	5529.00	1.00	10.24	0.4	0.4	109.5	0.30	4.0	0.005	0.08	0.4	8	<0.1	7065.0

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

JJ/nl

dt/msr-7513S

XLS/07

ECO TECH LABORATORY LTD.

10041 Dallas Drive

KAMLOOPS, B.C.

V2C 6T4

ICP CERTIFICATE OF ANALYSIS AW 2007- 7514

Aurora Geosciences

34a Laberge Rd

Whitehorse, YT

Y1A 5Y9

Phone: 250-573-5700

Fax : 250-573-4557

No. of samples received: 149

Sample Type: Core

Project: CWQ-7518-YT

Submitted by: Kel Sax

Values in ppm unless otherwise reported

Et #.	Tag #	Ag ppm	Al %	As ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppb	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P ppm	Pb ppm	S %	Sb ppm	Sc ppm	Se ppm	Sr ppm	Te ppm	Th ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
1	7R53939	0.1	0.33	1.0	39.5	0.24	0.12	0.20	8.0	112.0	31.99	1.97	1.1	15	0.10	14.0	0.08	455	0.67	0.031	20.8	147.0	21.76	0.10	0.02	1.4	0.3	16.5	0.08	11.6	0.001	0.10	0.7	<2	0.1	48.3
2	7R53940	0.1	0.29	0.9	34.5	0.40	0.09	0.11	6.4	152.0	18.94	1.47	1.2	10	0.01	15.0	0.05	425	0.73	0.028	16.0	130.0	23.72	0.10	0.06	2.7	0.3	10.5	0.08	9.4	0.001	0.16	0.6	<2	0.2	35.0
3	7R53941	0.1	0.34	1.2	39.0	0.26	0.13	0.12	12.1	137.0	20.89	1.72	1.4	10	0.02	16.5	0.09	567	0.97	0.028	23.9	221.0	21.05	0.08	0.04	2.6	0.4	16.5	0.10	11.3	0.001	0.14	1.2	<2	0.2	38.3
4	7R53942	0.1	0.33	2.1	39.0	0.32	0.14	0.10	9.0	122.0	17.99	1.69	1.5	15	0.02	16.5	0.07	505	0.88	0.035	18.8	221.0	22.76	0.08	0.06	2.9	0.4	18.5	0.12	11.6	0.001	0.12	1.2	<2	0.1	43.0
5	7R53943	0.1	0.37	3.0	37.0	0.30	0.32	0.09	7.1	125.5	14.80	1.53	1.5	10	0.01	15.5	0.15	480	1.24	0.033	14.3	180.0	22.96	0.08	0.06	2.7	0.3	33.5	0.10	10.9	0.002	0.12	1.2	<2	0.1	39.3
6	7R53944	0.1	0.48	1.6	46.0	0.36	0.13	0.08	9.2	102.0	25.97	2.32	2.0	10	0.02	16.5	0.31	477	0.56	0.028	19.1	174.0	20.98	0.16	0.04	2.7	0.3	15.0	0.10	11.3	0.001	0.14	2.2	2	0.1	59.1
7	7R53945	0.1	0.42	6.0	55.0	0.54	0.19	0.11	11.3	96.5	28.16	2.67	1.7	20	0.02	17.5	0.27	491	0.61	0.028	22.9	238.0	36.18	0.14	0.04	2.9	0.3	24.5	0.14	14.6	0.001	0.14	2.8	2	0.1	72.2
8	7R53946	0.1	0.37	3.2	42.0	0.24	0.42	0.08	7.6	121.5	22.44	1.52	1.5	10	0.02	15.0	0.22	432	0.62	0.033	17.5	152.0	18.29	0.14	0.04	2.5	0.3	44.5	0.10	11.2	0.002	0.12	1.8	<2	<0.1	45.3
9	7R53947	0.1	0.42	2.7	44.5	0.34	0.60	0.02	6.7	120.0	15.63	1.78	1.9	5	0.09	16.5	0.32	529	0.51	0.032	14.6	171.0	14.46	0.08	0.02	1.9	0.4	72.5	0.08	12.8	0.002	0.08	1.6	<2	<0.1	48.9
10	7R53948	0.1	0.73	4.8	62.0	0.50	0.22	0.04	12.0	101.0	29.07	2.65	2.9	5	0.13	19.0	0.44	447	0.75	0.033	24.9	254.0	21.42	0.16	0.02	2.2	0.5	31.0	0.08	15.9	0.002	0.12	3.0	2	<0.1	75.6
11	7R53949	0.1	0.38	2.3	38.5	0.22	0.21	0.02	5.3	126.5	10.69	1.66	1.6	10	0.07	17.5	0.13	527	0.71	0.031	12.3	127.0	9.43	0.02	0.04	1.8	0.4	29.5	0.04	12.6	0.001	0.06	1.2	<2	<0.1	42.6
12	7R53950	0.1	0.44	1.2	53.0	0.32	0.06	0.03	7.6	85.5	15.40	2.58	2.0	15	0.12	22.5	0.28	334	0.64	0.026	15.9	144.0	22.41	0.06	0.02	2.1	0.4	14.0	0.06	17.3	0.001	0.10	1.6	<2	<0.1	57.9
13	7R53951	0.1	0.47	1.6	51.0	0.44	0.08	0.05	12.1	108.0	29.61	2.65	2.3	10	0.11	18.5	0.22	275	0.46	0.031	24.4	327.0	17.33	0.12	0.02	2.0	0.5	17.0	0.06	13.2	0.002	0.10	1.5	<2	<0.1	69.8
14	7R53952	0.1	0.41	2.4	43.5	0.46	0.37	0.03	7.3	101.0	15.75	1.97	1.9	5	0.09	20.0	0.19	364	0.35	0.034	15.6	182.0	22.06	0.06	0.02	2.2	0.4	48.0	0.08	15.0	0.002	0.08	2.1	<2	<0.1	51.5
15	7R53953	0.1	0.41	1.9	49.0	0.36	0.30	0.04	6.7	101.5	19.53	2.15	1.8	15	0.10	20.5	0.31	337	0.34	0.033	14.8	202.0	15.87	0.14	0.04	1.9	0.4	44.0	0.08	17.5	0.002	0.08	1.8	<2	<0.1	51.3
16	7R53954	0.1	0.36	1.6	41.0	0.30	0.44	0.04	6.4	110.5	14.05	1.89	1.6	10	0.08	16.5	0.31	404	0.27	0.037	14.1	172.0	14.85	0.12	0.04	1.8	0.4	59.5	0.06	13.5	0.002	0.08	1.7	<2	<0.1	45.3
17	7R53955	0.1	0.41	1.9	50.5	0.30	0.28	0.02	7.6	100.5	14.26	2.13	1.8	20	0.09	20.0	0.35	414	0.29	0.032	16.1	166.0	12.03	0.12	0.04	1.8	0.4	39.0	0.06	17.8	0.001	0.08	2.0	<2	<0.1	60.6
18	7R53956	0.1	0.33	3.0	39.5	0.30	0.75	0.03	5.9	111.5	11.26	1.55	1.4	20	0.07	14.5	0.34	490	0.30	0.041	11.2	151.0	15.29	0.08	0.06	1.8	0.3	99.5	0.06	14.4	0.002	0.06	1.7	<2	<0.1	33.7
19	7R53957	0.1	0.38	3.9	36.5	0.28	0.52	0.03	6.0	120.0	9.40	1.46	1.6	25	0.07	19.0	0.23	427	0.33	0.039	11.4	160.0	13.38	0.08	0.06	1.9	0.4	68.0	0.06	16.9	0.003	0.06	1.5	<2	<0.1	32.0
20	7R53958	0.1	0.48	4.6	41.0	0.30	0.08	0.03	4.9	125.5	12.54	1.45	1.8	20	0.08	20.0	0.07	181	0.36	0.042	11.7	198.0	14.54	0.04	0.08	2.0	0.5	19.0	0.06	14.3	0.002	0.06	1.4	<2	<0.1	35.4
21	7R53959	0.1	0.45	1.7	73.5	0.32	0.06	0.05	10.3	111.0	17.99	2.61	1.9	25	0.08	25.0	0.05	747	0.39	0.034	20.6	205.0	15.38	<0.02	0.06	1.8	0.6	31.0	0.08	15.8	0.001	0.08	2.1	<2	<0.1	69.5
22	7R53960	0.1	0.44	3.5	54.5	0.44	0.05	0.03	7.9	118.0	18.70	1.88	1.9	20	0.11	21.0	0.15	166	0.34	0.031	17.1	168.0	20.35	0.08	0.04	1.9	0.5	12.0	0.06	16.3	0.002	0.08	1.6	<2	<0.1	53.6
23	7R53961	0.1	0.35	3.2	48.0	0.30	0.27	0.03	6.6	119.5	16.28	1.87	1.5	15	0.09	17.5	0.25	303	0.36	0.035	14.3	167.0	14.85	0.08	0.04	1.9	0.4	35.5	0.04	13.0	0.001	0.08	1.4	<2	<0.1	48.4
24	7R53962	0.1	0.30	3.5	40.0	0.24	0.52	0.02	5.0	118.0	12.78	1.52	1.2	15	0.08	14.5	0.26	420	0.31	0.038	10.5	149.0	10.34	0.10	0.04	1.8	0.4	60.5	0.06	12.1	0.001	0.06	1.1	<2	<0.1	31.3
25	7R53963	<0.1	0.37	2.1	39.0	0.28	0.30	0.02	6.0	126.5	12.67	1.65	1.6	10	0.08	15.0	0.29	438	0.36	0.036	12.7	152.0	11.96	0.12	0.02	1.8	0.3	37.5	0.04	12.6	0.002	0.06	1.4	<2	<0.1	37.0

ECO TECH LABORATORY LTD.

ICP CERTIFICATE OF ANALYSIS AW 2007- 7514

Aurora Geosciences

Ag Al As Ba Bi Ca Cd Co Cr Cu Fe Ga Hg K La Mg Mn Mo Na Ni P Pb S Sb Sc Se Sr Te Th Ti Tl U V W Zn

Et #.	Tag #	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppb	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm
26	7R53964	0.2	0.51	2.6	63.0	0.94	0.09	0.07	11.2	75.0	30.67	2.52	2.2	20	0.13	21.5	0.45	258	0.41	0.030	27.4	323.0	45.75	0.16	0.02	1.9	0.5	18.5	0.06	15.8	0.002	0.10	2.9	<2	<0.1	75.7							
27	7R53965	0.1	0.50	2.4	44.5	0.30	0.17	0.02	7.2	115.0	17.50	2.06	2.0	10	0.09	17.5	0.36	373	0.41	0.036	14.5	158.0	13.16	0.10	<0.02	1.8	0.4	22.0	0.06	13.5	0.002	0.08	1.8	<2	<0.1	49.1							
28	7R53966	0.1	0.49	5.1	54.5	0.40	0.32	0.04	9.4	113.0	20.45	1.98	2.1	15	0.11	20.0	0.37	443	0.47	0.037	19.6	177.0	16.61	0.10	<0.02	1.9	0.4	40.0	0.08	15.3	0.001	0.08	2.3	<2	<0.1	58.5							
29	7R53967	0.1	0.72	2.7	57.0	0.50	0.16	0.08	11.4	98.0	29.80	2.77	2.6	20	0.13	18.5	0.50	367	0.46	0.032	26.7	249.0	24.68	0.20	0.04	2.0	0.5	22.5	0.04	15.7	0.002	0.10	2.4	4	<0.1	78.6							
30	7R53968	0.1	0.46	4.5	50.5	0.30	0.29	0.06	9.6	112.5	21.39	2.34	1.7	15	0.10	16.0	0.42	485	0.36	0.035	19.1	183.0	13.71	0.22	0.04	1.8	0.4	35.5	0.06	14.1	0.001	0.10	2.3	<2	<0.1	57.0							
31	7R53969	0.1	0.37	2.6	40.0	0.32	0.58	0.06	6.5	104.5	14.81	1.98	1.5	20	0.08	15.0	0.42	619	0.28	0.034	15.0	154.0	15.15	0.14	0.04	2.0	0.3	59.0	0.04	13.7	0.001	0.08	2.1	<2	<0.1	49.0							
32	7R53970	0.2	0.49	1.1	53.5	0.50	0.14	0.08	12.1	79.5	35.51	2.99	1.7	35	0.11	14.0	0.52	378	0.37	0.031	25.8	295.0	16.96	0.52	0.04	1.9	0.4	18.5	0.06	14.8	0.001	0.10	2.3	<2	<0.1	90.7							
33	7R53971	0.1	0.42	1.5	43.5	0.38	0.38	0.10	11.7	95.5	27.26	2.99	1.3	60	0.10	9.5	0.41	390	0.67	0.034	24.6	304.0	22.77	0.84	0.06	1.8	0.6	41.0	0.08	11.9	0.001	0.08	2.3	<2	<0.1	63.6							
34	7R53972	0.1	0.44	5.6	39.0	0.10	0.80	0.19	7.6	117.5	19.88	2.13	1.3	25	0.06	8.5	0.46	854	0.43	0.034	20.4	212.0	6.16	0.18	0.06	2.2	0.4	87.0	0.06	4.9	0.001	0.04	1.1	<2	<0.1	41.8							
35	7R53973	0.1	0.38	6.1	27.5	0.06	0.81	0.11	4.6	124.5	10.66	1.27	1.0	10	0.03	8.5	0.40	625	0.42	0.037	12.7	182.0	7.04	0.04	0.04	1.7	0.2	98.0	0.06	3.4	0.001	0.02	0.6	<2	<0.1	21.6							
36	7R53974	0.1	0.40	6.0	24.5	0.08	0.95	0.17	4.5	139.0	11.17	1.49	1.1	10	0.04	9.0	0.42	793	0.43	0.043	12.9	243.0	6.05	0.04	0.06	1.8	0.3	107.0	0.06	3.3	0.001	0.04	0.7	<2	<0.1	26.0							
37	7R53975	0.1	0.38	4.0	47.0	0.14	0.96	0.46	9.6	121.5	23.09	2.22	1.2	30	0.07	7.5	0.57	1090	0.49	0.041	28.2	280.0	6.31	0.38	0.12	1.9	0.4	127.0	0.06	3.7	0.001	0.06	1.0	<2	<0.1	38.3							
38	7R53976	0.2	0.71	9.5	70.5	0.28	0.49	0.16	17.9	78.5	40.74	4.36	2.2	40	0.10	14.5	1.00	943	0.42	0.041	46.1	738.0	23.06	0.24	0.08	2.7	0.5	77.5	0.08	6.1	0.002	0.08	1.6	6	<0.1	94.0							
39	7R53977	0.1	0.48	6.0	37.5	0.08	0.12	0.07	4.8	145.5	10.49	1.23	1.3	10	0.05	10.0	0.14	158	0.33	0.047	12.4	231.0	3.94	<0.02	0.26	1.9	0.3	20.0	<0.02	3.4	0.001	0.04	0.6	<2	<0.1	20.8							
40	7R53978	0.1	0.52	6.7	51.0	0.12	0.33	0.14	7.2	143.0	18.42	2.07	1.6	15	0.07	12.5	0.29	428	0.50	0.032	20.8	367.0	8.77	0.04	0.20	1.9	0.4	41.0	0.04	5.0	0.002	0.06	0.8	2	<0.1	38.8							
41	7R53979	0.1	0.66	6.3	45.5	0.12	0.07	0.34	7.4	146.0	21.64	2.28	1.8	45	0.07	14.5	0.10	188	0.31	0.035	26.7	289.0	8.49	<0.02	0.08	2.1	0.4	16.5	0.04	5.2	0.001	0.04	1.0	<2	<0.1	112.8							
42	7R53980	0.1	0.56	6.6	38.5	0.08	0.65	0.16	5.5	157.5	11.30	1.53	1.5	15	0.06	11.5	0.37	490	0.36	0.044	16.1	213.0	5.57	0.04	0.06	2.1	0.4	69.5	0.04	4.0	0.002	0.04	0.7	<2	<0.1	43.9							
43	7R53981	0.2	1.10	6.1	63.0	0.30	0.42	0.29	17.4	97.5	42.47	4.43	3.2	50	0.10	24.5	0.73	1647	0.64	0.045	50.9	616.0	25.06	0.32	0.14	2.8	0.7	60.0	0.10	9.9	0.002	0.08	1.7	8	<0.1	99.6							
44	7R53982	0.1	0.88	6.6	53.5	0.12	0.70	0.17	13.0	94.0	28.82	2.91	2.4	40	0.09	27.0	0.47	1164	0.59	0.031	34.9	441.0	8.06	0.30	0.12	2.1	0.8	84.5	0.06	9.9	0.001	0.06	1.6	2	<0.1	66.5							
45	7R53983	0.1	1.16	10.4	69.5	0.24	0.27	0.09	17.9	44.5	48.99	4.61	3.2	50	0.11	39.5	0.82	689	0.33	0.041	49.6	678.0	16.98	0.18	0.08	2.6	0.9	42.0	0.08	14.7	0.001	0.08	2.0	6	<0.1	120.1							
46	7R53984	0.1	0.99	10.9	65.0	0.24	0.37	0.21	14.6	94.5	47.46	4.61	3.4	20	0.10	37.0	1.12	735	0.40	0.035	43.9	657.0	12.16	0.12	0.08	2.4	0.8	54.0	0.08	14.0	0.002	0.08	2.4	10	<0.1	105.5							
47	7R53985	0.2	1.09	10.0	65.0	0.30	0.47	0.22	17.1	70.5	56.35	5.58	3.8	20	0.10	35.0	1.38	858	0.36	0.038	55.1	633.0	16.88	0.20	0.12	2.6	0.8	62.5	0.08	14.7	0.002	0.08	2.4	14	<0.1	128.4							
48	7R53986	0.1	0.92	4.6	71.0	0.24	0.31	0.09	15.2	46.5	40.55	5.57	3.1	35	0.10	33.5	1.31	698	0.30	0.033	53.6	613.0	14.70	0.30	0.20	2.6	0.7	47.5	0.06	14.0	0.002	0.08	2.5	12	<0.1	133.2							
49	7R53987	0.1	0.52	6.6	71.5	0.22	0.63	0.15	16.8	96.5	47.70	4.44	2.1	55	0.10	27.0	1.08	831	0.66	0.033	47.8	528.0	11.78	0.44	0.24	2.1	0.7	79.5	0.06	11.9	0.001	0.08	1.1	2	<0.1	98.1							
50	7R53988	0.1	0.51	7.2	63.5	0.22	1.12	0.24	9.2	97.5	25.72	3.01	1.9	30	0.09	24.5	0.69	1040	0.35	0.036	25.3	323.0	12.62	0.16	0.18	2.5	0.6	130.5	0.08	9.7	0.001	0.08	0.9	<2	<0.1	59.9							
51	7R53989	0.1	0.34	6.0	55.0	0.08	1.43	0.30	7.0	121.0	18.15	2.24	1.4	25	0.08	16.5	0.70	1306	0.33	0.037	18.4	246.0	2.71	0.22	0.14	1.7	0.4	164.0	0.06	7.0	0.001	0.06	0.9	<2	<0.1	42.2							
52	7R53990	0.1	0.60	13.2	80.0	0.36	1.19	0.28	15.7	82.0	36.24	3.13	2.2	30	0.11	29.0	0.82	1156	0.28	0.034	36.3	392.0	27.59	0.24	0.18	2.2	0.7	129.0	0.10	12.9	0.002	0.08	1.5	2	<0.1	62.8							
53	7R53991	0.1	0.51	3.9	56.0	0.16	0.72	0.09	7.7	126.0	20.13	2.02	1.6	40	0.09	19.0	0.43	625	0.39	0.035	20.9	385.0	7.98	0.36	0.12	1.9	0.5	67.0	0.04	8.5	0.002	0.06	0.9	<2	<0.1	39.0							
54	7R53992	0.1	0.61	8.0	76.5	0.22	0.90	0.22	12.3	99.5	26.08	2.56	2.3	35	0.10	32.5	0.56	891	0.68	0.037	30.5	484.0	18.99	0.22	0.10	1.8	0.7	84.0	0.08	11.8	0.002	0.08	1.1	<2	<0.1	52.2							
55	7R53993	0.1	1.08	13.9	83.0	0.26	0.79	0.12	15.2	75.0	35.43	3.31	4.4	15	0.12	44.0	0.93	659	0.51	0.044	37.0	640.0	15.14	0.28	0.08	2.0	1.0	67.5	0.08	16.1	0.003	0.10	1.8	6	<0.1	72.7							
56	7R53994	0.1	1.15	6.5	69.5	0.24	1.05	0.14	14.5	64.5	40.83	3.94	4.3	20	0.11	35.0	1.09	609	0.66	0.035	41.6	610.0	7.46	0.68	0.12	2.1	0.9	83.5	0.08	15.2	0.003	0.10	1.8	6	<0.1	89.1							
57	7R53995	0.1	0.45	11.0	68.5	0.32	5.21	0.24	17.2	52.5	46.45	4.20	1.8	45	0.10	22.5	1.06	1186	0.86	0.028	43.2	629.0	18.07	1.22	0.30	2.6	1.2	389.0	0.14	12.8	0.003	0.10	1.0	<2	<0.1	66.4							
58	7R53996	<0.1	0.32	14.3	37.0	0.08	5.24	0.05	7.7	98.5	12.95	1.95	1.2	10	0.03	15.5	0.49	957	0.38	0.028	22.5	367.0	3.69	0.18	0.10	2.2	0.6	373.0	0.12	6.3	0.001	0.04	0.5	<2	<0.1	25.5							
59	7R53997	0.1	0.43	12.5	73.0	0.24	5.91	0.14	13.4	62.0	32.72	3.14	2.0	45	0.09	26.5	0.70	826	0.58	0.037	36.7	587.0	12.41	0.96	0.20	2.8	0.9	369.5	0.12	11.5	0.002	0.08	1.1	<2	<0.1	46.9							
60	7R53998	<0.1	0.23	6.1	34.5	0.06	2.27	0.02	3.8	131.0	7.78	1.01	1.1	10	0.04	11.5	0.22	291	0.37	0.042	12.3	182.0	0.25	0.14	0.08	1.6	0.4	185.5	0.06	5.0	0.002	0.06	0.6	<2	<0.1	15.2							
61	7R53999	0.2	0.33	6.8	63.5	0.10	2.15	0.07	6.4	125.0	13.23	1.40	1.5	15	0.08	18.5	0.34	556	0.65	0.031	17.5	266.0	6.18	0.14	0.10	1.9	0.4	174.5	0.08	7.0	0.003	0.08	0.6	<2	<0.1	22.8							

66	7R54004	0.2	2.41	30.9	58.5	0.36	0.35	0.17	22.6	76.5	62.39	6.28	8.2	35	0.09	15.5	1.98	797	1.70	0.045	61.1	656.0	19.30	0.80	0.16	3.1	0.8	38.5	0.12	13.5	0.004	0.10	2.0	26	<0.1	144.4
67	7R54005	0.2	2.49	12.1	58.0	0.28	0.30	0.13	20.4	78.0	57.07	5.99	8.3	25	0.09	11.0	1.88	769	1.51	0.038	57.1	618.0	17.21	0.64	0.12	2.9	0.7	28.0	0.06	13.4	0.004	0.08	2.0	26	<0.1	139.0
68	7R54006	0.2	2.58	7.5	50.0	0.42	0.29	0.21	23.1	78.5	74.60	6.84	8.4	35	0.10	9.5	1.93	767	1.56	0.039	66.7	661.0	25.25	1.32	0.30	3.0	0.9	26.5	0.10	15.3	0.004	0.08	1.9	26	<0.1	143.5
69	7R54007	0.1	1.01	13.5	48.5	0.14	2.26	0.09	10.0	106.5	28.85	3.37	3.6	20	0.07	10.5	1.16	1338	0.72	0.045	29.5	556.0	7.09	0.36	0.12	2.2	0.5	228.0	0.10	8.5	0.002	0.06	1.3	6	<0.1	64.9
70	7R54008	0.1	1.14	8.4	50.5	0.20	1.68	0.22	14.8	105.0	33.04	3.91	4.0	25	0.08	12.5	1.15	1134	0.92	0.045	32.0	498.0	9.88	1.12	0.30	2.3	0.8	157.5	0.10	9.9	0.003	0.06	1.3	8	<0.1	71.2
71	7R54009	0.2	0.65	3.8	34.0	0.28	1.03	0.27	16.6	95.5	38.80	3.66	2.4	30	0.08	16.5	0.71	731	1.04	0.029	39.6	427.0	22.26	1.70	0.32	1.7	1.1	99.5	0.08	10.8	0.003	0.08	1.5	4	<0.1	69.5
72	7R54010	0.2	0.62	5.4	47.0	0.20	1.49	0.15	9.6	103.5	29.13	2.66	2.3	20	0.07	16.0	0.60	537	0.57	0.030	32.0	345.0	10.40	1.06	0.18	1.7	0.7	143.0	0.10	8.3	0.002	0.06	1.2	2	<0.1	55.8
73	7R54011	0.1	0.52	8.8	59.5	0.16	3.35	0.08	7.5	91.0	20.82	2.00	2.0	10	0.08	17.0	0.55	430	0.48	0.030	23.6	382.0	9.69	0.50	0.14	1.7	0.6	264.5	0.08	8.9	0.002	0.08	1.1	<2	<0.1	32.1
74	7R54012	0.1	1.05	12.9	66.0	0.20	3.49	0.18	11.3	79.0	38.09	2.87	3.8	15	0.09	22.0	0.90	669	0.52	0.036	30.7	504.0	11.15	0.52	0.12	2.3	0.7	288.0	0.12	11.7	0.006	0.08	1.4	6	<0.1	55.8
75	7R54013	0.1	2.13	9.1	70.0	0.28	0.27	0.12	16.7	83.5	45.94	4.34	7.7	15	0.11	37.0	1.42	485	0.39	0.033	44.2	554.0	16.36	0.26	0.12	2.6	0.9	34.5	0.06	14.7	0.008	0.10	1.6	18	<0.1	97.6
76	7R54014	0.1	2.50	13.2	73.5	0.28	0.60	0.23	18.0	80.5	54.00	5.17	8.9	15	0.11	42.0	1.69	785	0.44	0.044	49.5	642.0	15.39	0.12	0.08	2.8	0.9	78.0	0.08	15.9	0.005	0.10	1.7	22	<0.1	118.6
77	7R54015	0.1	1.07	8.8	59.0	0.30	1.18	0.21	14.4	93.5	43.60	4.18	3.7	30	0.09	20.0	1.16	1095	0.74	0.045	42.0	487.0	20.51	0.60	0.18	2.3	0.7	114.0	0.10	11.8	0.002	0.08	1.8	8	<0.1	86.7
78	7R54016	0.1	0.78	4.8	38.5	0.36	0.08	0.03	5.5	131.5	30.79	1.72	2.3	25	0.09	26.0	0.12	81	0.34	0.031	17.8	224.0	16.86	0.14	0.10	1.7	0.6	25.0	0.04	14.9	0.001	0.06	1.3	2	<0.1	57.1
79	7R54017	0.1	0.70	6.7	70.5	0.48	0.04	0.08	11.4	120.5	20.40	2.91	2.7	30	0.10	36.5	0.09	846	0.36	0.033	20.6	218.0	23.76	<0.02	0.10	1.5	0.7	26.5	0.06	19.7	0.001	0.10	1.8	<2	<0.1	64.5
80	7R54018	0.1	0.72	3.0	54.5	0.52	0.06	0.03	12.7	83.0	29.14	2.98	3.0	20	0.11	39.0	0.26	445	0.36	0.030	26.4	243.0	19.77	0.12	0.06	1.4	0.7	19.5	0.04	20.3	0.002	0.12	3.1	<2	<0.1	90.5
81	7R54019	0.1	0.67	4.4	46.0	0.60	0.03	0.07	11.9	80.0	31.87	3.84	3.0	25	0.09	37.5	0.11	485	0.35	0.029	26.8	240.0	26.17	0.02	0.06	1.5	0.7	18.0	0.04	18.5	0.001	0.10	2.9	<2	<0.1	99.7
82	7R54020	0.1	0.50	3.1	63.5	0.74	<0.01	0.06	21.4	88.0	37.90	4.44	3.0	35	0.10	49.5	0.04	733	0.49	0.030	30.2	288.0	28.33	<0.02	0.12	1.4	0.8	25.5	0.06	20.9	0.001	0.16	2.8	<2	<0.1	103.5
83	7R54021	0.1	0.60	3.5	46.5	0.66	0.03	0.04	11.5	90.0	34.55	3.52	2.8	30	0.10	43.0	0.06	218	0.50	0.032	28.8	272.0	30.75	<0.02	0.12	1.5	0.7	17.0	0.04	19.9	0.001	0.12	2.6	<2	<0.1	105.1
84	7R54022	0.1	0.71	3.2	47.5	0.48	0.05	0.05	8.1	134.0	20.66	2.75	2.6	25	0.09	36.0	0.12	1152	0.45	0.032	21.5	221.0	21.56	<0.02	0.06	1.4	0.6	23.0	0.04	17.4	0.001	0.10	1.9	<2	<0.1	73.9
85	7R54023	0.1	0.72	4.7	42.5	0.60	0.05	0.05	12.6	115.0	30.28	3.35	2.7	30	0.09	36.5	0.11	609	0.54	0.031	37.4	262.0	26.79	<0.02	0.14	1.7	0.7	21.5	0.06	18.0	0.001	0.10	2.5	4	<0.1	102.1
86	7R54024	0.1	0.78	2.7	45.0	0.64	0.06	0.03	8.6	97.5	24.99	1.99	3.4	25	0.12	42.0	0.13	367	0.30	0.031	18.5	290.0	28.53	<0.02	0.06	1.7	0.8	22.0	0.06	18.5	0.002	0.10	1.8	4	<0.1	80.8
87	7R54025	0.1	0.64	3.4	51.5	0.68	0.05	0.06	12.6	69.0	32.95	6.04	3.5	25	0.09	47.5	0.08	686	0.40	0.026	31.8	315.0	25.84	<0.02	0.04	1.2	0.8	22.0	0.06	21.7	0.001	0.12	2.9	2	<0.1	125.7
88	7R54026	0.1	0.63	3.0	55.0	0.84	0.08	0.03	12.2	78.0	29.66	3.78	3.2	25	0.11	51.5	0.07	551	0.35	0.029	26.1	292.0	31.14	<0.02	0.04	1.4	0.8	22.5	0.06	23.1	0.001	0.12	3.1	2	<0.1	111.2
89	7R54027	0.1	0.76	1.8	33.0	0.30	0.04	0.03	6.0	102.0	12.74	1.92	2.3	25	0.06	27.0	0.14	427	0.24	0.027	14.8	212.0	16.48	<0.02	0.06	1.0	0.5	13.5	0.04	15.3	0.001	0.06	2.3	<2	<0.1	51.8
90	7R54028	0.1	0.81	3.2	41.0	0.54	0.06	0.03	9.2	93.5	25.54	2.07	2.8	25	0.09	36.0	0.13	229	0.32	0.030	19.3	277.0	26.96	<0.02	0.06	1.4	0.6	17.0	0.04	17.6	0.001	0.10	2.4	4	<0.1	72.6
91	7R54029	0.1	0.99	4.4	49.5	0.50	0.09	0.03	8.4	89.0	23.41	2.81	3.0	20	0.09	35.5	0.20	437	0.22	0.029	20.2	288.0	24.34	<0.02	0.06	1.2	0.7	20.0	0.04	17.4	0.001	0.08	2.5	2	<0.1	80.3
92	7R54030	0.1	0.75	6.3	66.0	0.72	0.05	0.05	15.6	67.5	35.38	4.13	3.4	25	0.11	53.0	0.09	711	0.27	0.029	34.0	378.0	25.98	<0.02	0.08	1.4	0.9	21.0	0.06	22.0	0.002	0.14	2.6	2	<0.1	117.2
93	7R54031	0.1	0.68	3.0	53.5	0.82	0.05	0.09	25.7	35.0	67.07	3.96	3.1	25	0.10	46.5	0.14	1271	0.42	0.029	42.5	374.0	38.74	<0.02	0.26	1.6	0.8	15.0	0.06	20.1	0.002	0.18	2.5	2	<0.1	117.7
94	7R54032	0.1	1.10	4.5	54.5	0.44	0.15	0.05	8.9	73.0	24.79	3.05	3.0	30	0.10	36.0	0.19	645	0.19	0.032	21.0	370.0	22.68	<0.02	0.08	1.3	0.7	23.0	0.06	17.8	0.002	0.10	1.6	2	<0.1	87.1
95	7R54033	0.1	0.68	3.0	42.0	0.40	0.13	0.04	12.9	113.0	22.26	2.29	2.1	40	0.08	27.0	0.13	641	0.18	0.032	22.9	312.0	19.47	<0.02	0.26	2.9	0.6	15.5	0.06	13.2	0.001	0.08	0.9	<2	<0.1	64.3
96	7R54034	0.1	0.45	17.2	39.5	0.32	7.64	0.10	13.0	76.5	18.68	2.53	1.4	30	0.05	19.0	0.10	825	0.20	0.025	24.1	622.0	18.50	<0.02	0.32	3.1	0.8	79.5	0.06	11.2	0.001	0.06	0.7	<2	0.5	53.8
97	7R54035	0.1	0.27	35.1	35.0	0.28	>10	0.12	7.2	28.5	14.06	1.68	1.0	20	0.02	22.5	0.13	777	0.08	0.025	17.6	365.0	16.24	<0.02	0.12	2.5	0.9	335.5	0.12	7.8	0.001	0.04	0.7	<2	<0.1	34.4
98	7R54036	0.1	0.62	1.9	55.0	0.70	0.18	0.06	9.9	68.5	43.74	3.68	3.2	50	0.11	65.5	0.08	451	0.32	0.030	25.9	291.0	26.73	<0.02	0.18	2.2	1.5	12.0	0.08	25.2	0.001	0.10	1.7	<2	<0.1	90.0
99	7R54037	0.1	0.64	1.5	44.5	0.46	0.13	0.04	6.8	76.5	28.59	2.64	2.5	30	0.09	43.0	0.09	446	0.23	0.030	19.5	200.0	23.13	<0.02	0.08	1.8	0.9	11.5	0.04	18.2	0.001	0.08	1.2	<2	<0.1	63.2
100	7R54038	0.1	0.63	3.4	64.5	0.54	0.06	0.08	13.1	58.5	40.82	4.99	3.2	35	0.09	60.5	0.08	419	0.28	0.030	24.8	284.0	23.04	<0.02	0.10	1.4	1.1	23.5	0.06	25.1	0.001	0.10	2.7	<2	<0.1	100.8
101	7R54039	0.1	0.69	7.5	51.0	0.42	0.04	0.08	16.5	76.5	33.43	3.74	3.1	20	0.09	47.5	0.06	264	0.29	0.030	31.9	229.0	20.08	<0.02	0.06	1.4	0.9	21.5	0.06	20.0	0.001	0.08	2.8	<2	<0.1	128.6
102	7R54040	0.1	0.71	2.6	40.0	0.24	0.11	0.03	7.1	117.0	13.94	2.01	2.0	15	0.07	23.5	0.13	608	0.19	0.029	12.5	148.0	15.24	<0.02	0.04	1.1	0.5	19.0</								

107	7R54045	0.1	0.59	5.3	46.5	0.26	0.11	0.05	9.8	80.0	21.51	2.20	2.6	20	0.22	31.5	0.11	323	0.37	0.019	17.7	162.0	20.79	0.04	0.04	0.9	0.5	14.0	0.04	12.9	0.001	0.06	1.0	4	<0.1	61.3
108	7R54046	0.1	0.52	5.0	50.0	0.36	0.14	0.05	13.1	85.5	27.25	2.38	2.3	25	0.25	32.0	0.09	279	0.46	0.022	21.4	170.0	29.64	0.06	0.02	0.9	0.4	13.5	0.04	14.2	0.001	0.08	1.3	4	<0.1	70.6
109	7R54047	0.1	0.43	4.4	32.0	0.20	0.44	0.03	5.6	115.0	14.35	1.36	1.6	15	0.16	21.5	0.06	351	0.29	0.026	9.9	135.0	17.27	<0.02	0.04	0.7	0.3	11.0	0.02	9.2	0.001	0.06	0.6	2	<0.1	38.4
110	7R54048	0.1	0.31	0.9	41.5	0.48	0.03	0.01	1.1	105.5	8.52	1.62	1.9	45	0.25	33.5	0.02	22	0.51	0.021	3.7	187.0	31.43	0.06	0.08	0.7	0.5	37.0	0.04	11.2	0.001	0.08	0.8	2	<0.1	7.3
111	7R54049	0.1	0.36	3.3	30.5	0.20	0.35	0.04	6.0	153.0	17.97	1.70	1.4	20	0.16	18.0	0.06	462	0.36	0.022	12.1	150.0	17.62	0.04	0.06	1.0	0.3	17.0	0.02	9.7	0.001	0.06	0.8	2	<0.1	39.6
112	7R54050	0.1	0.33	4.0	37.0	0.32	1.19	0.06	9.2	107.5	19.56	1.99	1.3	20	0.21	16.0	0.22	451	0.43	0.023	15.9	142.0	22.97	0.08	0.04	1.0	0.3	46.0	0.04	10.4	0.001	0.08	1.3	2	<0.1	56.6
113	7R54051	0.1	0.33	6.5	36.0	0.26	1.12	0.06	8.0	140.0	16.41	1.75	1.3	15	0.20	16.5	0.30	459	0.43	0.024	13.7	127.0	21.29	0.10	0.04	0.9	0.3	73.0	0.04	10.0	0.001	0.06	1.0	2	<0.1	48.6
114	7R54052	0.1	0.37	2.8	38.5	0.58	0.37	0.07	14.8	66.5	40.46	3.22	1.4	30	0.24	13.0	0.32	409	0.50	0.022	30.6	184.0	33.75	0.88	0.06	1.2	0.3	28.0	0.04	12.3	0.001	0.08	1.4	4	<0.1	78.1
115	7R54053	0.1	0.79	1.7	38.0	0.46	0.13	0.14	12.7	84.0	33.84	2.67	2.6	20	0.25	20.5	0.36	347	0.45	0.023	30.7	250.0	26.52	0.54	0.04	1.0	0.4	15.5	0.04	12.7	0.001	0.08	2.0	6	<0.1	94.8
116	7R54054	0.1	1.23	4.4	45.5	0.60	0.11	0.12	14.7	71.0	41.46	3.65	4.4	20	0.28	34.0	0.51	267	0.50	0.024	33.8	283.0	34.38	0.20	0.04	1.3	0.6	16.5	0.06	17.3	0.002	0.06	2.3	8	<0.1	114.8
117	7R54055	0.1	0.98	3.2	37.5	0.44	0.16	0.08	12.9	72.5	27.44	2.92	3.7	15	0.24	39.0	0.30	808	0.32	0.023	23.3	223.0	28.62	0.02	0.06	1.0	0.6	24.0	0.04	15.4	0.001	0.06	1.3	6	<0.1	83.3
118	7R54056	0.1	0.73	2.6	38.0	0.38	0.10	0.04	4.2	94.0	24.15	2.41	3.3	15	0.24	41.0	0.20	80	0.42	0.021	11.0	271.0	26.34	0.04	0.06	0.9	0.6	28.5	0.04	15.5	0.001	0.08	1.6	6	<0.1	49.1
119	7R54057	0.1	1.12	4.2	39.0	0.56	0.18	0.09	5.7	73.0	37.75	2.96	4.3	15	0.25	43.0	0.32	95	0.44	0.024	17.4	514.0	35.18	0.02	0.06	1.2	0.7	43.5	0.04	16.8	0.002	0.10	2.3	8	<0.1	77.8
120	7R54058	0.1	0.85	3.4	40.0	0.46	0.15	0.09	8.7	87.5	30.68	2.67	3.5	15	0.24	40.0	0.18	101	0.51	0.024	19.7	488.0	27.55	0.04	0.06	1.1	0.6	30.0	0.04	15.7	0.001	0.08	1.8	6	<0.1	79.5
121	7R54059	<0.1	0.63	2.8	38.5	0.24	0.14	0.06	10.4	82.0	16.47	1.80	2.3	10	0.18	27.0	0.11	687	0.22	0.025	16.4	241.0	20.60	<0.02	0.04	0.7	0.4	18.0	0.02	11.9	0.001	0.06	0.7	4	<0.1	54.5
122	7R54060	0.1	0.73	3.5	45.0	0.32	0.13	0.06	10.4	76.5	25.82	2.20	2.7	15	0.21	31.5	0.15	450	0.20	0.024	22.1	199.0	21.83	<0.02	0.04	0.8	0.5	18.0	0.04	13.4	0.001	0.08	0.8	4	<0.1	71.2
123	7R54061	<0.1	0.93	3.1	40.0	0.36	0.18	0.06	11.9	82.5	30.78	2.92	3.4	15	0.21	36.5	0.28	535	0.26	0.022	24.9	261.0	24.45	<0.02	0.08	1.1	0.5	17.5	0.04	14.6	0.001	0.08	0.9	6	<0.1	82.5
124	7R54062	0.1	0.97	2.7	43.0	0.38	0.15	0.05	11.4	90.5	34.28	3.08	3.2	20	0.24	37.0	0.28	358	0.33	0.025	23.0	242.0	25.24	<0.02	0.08	1.1	0.5	14.0	0.04	16.2	0.002	0.08	1.3	6	<0.1	77.7
125	7R54063	0.1	1.13	4.3	39.0	0.40	>10	0.08	10.3	52.5	28.61	3.77	3.3	20	0.20	35.0	0.44	864	0.31	0.025	24.7	816.0	26.64	0.02	0.12	2.4	0.6	111.0	0.04	14.9	0.001	0.08	1.8	4	<0.1	60.5
126	7R54064	0.1	0.29	3.9	36.0	0.26	>10	0.11	10.3	77.0	24.74	2.14	1.2	25	0.15	18.5	0.11	1032	0.19	0.021	22.5	317.0	21.31	0.02	0.34	2.2	0.4	125.5	0.02	7.0	0.005	0.06	0.6	4	<0.1	44.9
127	7R54065	0.1	0.45	1.1	41.5	0.46	0.62	0.08	19.1	67.5	47.21	3.78	2.2	55	0.23	35.5	0.06	530	0.23	0.022	36.2	384.0	34.85	<0.02	0.14	1.8	0.5	19.0	0.04	13.5	0.005	0.08	1.0	6	<0.1	94.1
128	7R54066	0.1	0.47	0.8	47.5	0.44	0.16	0.11	21.8	91.0	39.87	2.86	2.3	55	0.25	37.5	0.06	681	0.26	0.023	30.2	238.0	29.09	<0.02	0.08	1.3	0.5	17.5	0.04	14.1	0.001	0.08	1.0	4	<0.1	93.3
129	7R54067	0.1	0.76	0.7	47.0	0.34	0.17	0.09	20.2	78.5	43.59	3.35	2.7	20	0.19	26.5	0.19	1287	0.30	0.024	29.6	348.0	29.90	<0.02	0.06	1.3	0.5	26.0	0.04	11.1	0.001	0.08	0.9	6	<0.1	85.6
130	7R54068	0.1	1.67	0.7	75.0	0.30	0.31	0.03	21.3	56.5	27.18	5.00	5.3	15	0.22	30.5	0.67	2282	0.27	0.025	50.0	562.0	19.57	<0.02	0.04	1.9	0.5	49.5	0.04	12.6	0.001	0.10	0.8	14	<0.1	114.9
131	7R54069	0.1	1.33	0.7	35.5	0.24	0.26	0.04	16.8	77.5	29.67	3.64	4.1	15	0.19	19.0	0.52	865	0.27	0.025	32.9	298.0	21.19	0.02	0.06	1.6	0.3	22.0	0.02	8.7	0.001	0.06	0.6	12	<0.1	79.6
132	7R54070	0.1	1.71	0.5	37.0	0.24	0.34	0.03	18.2	73.0	38.70	4.33	5.3	10	0.21	23.0	0.70	450	0.27	0.029	38.3	475.0	16.76	<0.02	0.06	1.7	0.4	27.0	0.04	9.9	0.002	0.06	0.6	16	<0.1	93.8
133	7R54071	0.1	0.89	2.2	35.5	0.48	0.23	0.04	12.8	95.5	34.59	2.91	3.0	40	0.20	25.0	0.29	372	0.69	0.026	23.4	204.0	44.02	0.02	0.06	1.3	0.4	19.0	0.04	8.8	0.001	0.06	0.5	8	<0.1	78.6
134	7R54072	0.1	0.60	0.7	33.5	0.32	0.98	0.11	13.8	98.0	48.80	2.99	2.1	20	0.21	22.0	0.18	450	0.66	0.028	24.6	318.0	26.25	0.06	0.08	1.4	0.5	30.5	0.02	10.3	0.001	0.06	0.9	4	<0.1	73.0
135	7R54073	0.1	1.04	0.5	37.0	0.42	0.12	0.05	6.7	115.5	40.44	3.26	3.4	15	0.21	20.5	0.41	143	0.67	0.025	15.4	405.0	38.57	0.06	0.06	1.2	0.4	40.0	0.02	8.9	0.001	0.06	1.2	8	<0.1	60.5
136	7R54074	0.1	1.20	2.6	39.5	0.20	0.22	0.03	14.2	113.0	30.75	3.26	3.8	10	0.20	18.5	0.54	256	0.37	0.028	27.9	217.0	17.36	0.04	0.04	1.2	0.3	24.0	<0.02	8.1	0.001	0.06	0.7	10	<0.1	63.9
137	7R54075	0.1	0.20	2.5	26.5	0.08	0.03	0.05	7.8	152.0	9.12	2.04	1.0	<5	0.05	13.5	0.02	338	0.44	0.037	16.5	116.0	12.17	<0.02	0.10	1.0	0.3	5.5	<0.02	6.8	0.005	0.02	0.7	4	<0.1	35.7
138	7R54076	0.1	0.26	3.3	34.5	0.42	0.02	0.04	13.2	94.0	27.32	3.04	1.6	<5	0.11	30.5	0.03	280	0.51	0.034	28.9	143.0	25.50	<0.02	0.16	1.5	0.4	10.0	0.04	12.8	0.005	0.04	1.1	6	<0.1	63.1
139	7R54077	0.1	0.29	3.3	33.0	0.20	0.02	0.03	12.0	118.0	25.02	3.01	1.6	10	0.11	27.5	0.03	216	0.56	0.038	26.2	110.0	16.73	0.02	0.14	1.4	0.4	10.0	0.04	12.2	0.005	0.04	1.0	6	<0.1	61.6
140	7R54078	0.1	0.27	5.1	50.5	0.32	0.03	0.11	15.9	103.5	23.00	2.96	1.4	10	0.11	25.0	0.03	806	0.53	0.042	30.4	130.0	27.64	<0.02	0.14	1.2	0.4	10.0	0.04	12.0	0.005	0.06	1.0	4	<0.1	73.1
141	7R54079	0.1	0.27	8.1	37.5	0.40	0.04	0.04	8.4	126.5	22.51	2.31	1.3	10	0.10	20.0	0.03	302	0.72	0.040	17.2	161.0	28.15	0.02	0.24	1.4	0.3	15.5	0.06	8.7	0.005	0.04	0.7	4	<0.1	38.7
142	7R54080	0.1	0.28	11.5	34.0	0.26	0.05	0.06	17.0	85.5	36.45	3.72	1.6	5	0.11	32.5	0.03	543	1.08	0.039	32.2	258.0	23.21	0.02	0.22	1.9	0.6	10.0	0.06	13.2	0.005	0.04	1.1	4	<0.1	80.7
143	7R54081	0.1	0.26	5.2	34.0	0.18	0.03	0.09	11.7	107.5	30.86	2.53	1.2	5	0.10	20.0	0.02	563	0.68	0.040	22.3	168.0	17.87	0.02	0.18	1.2	0.4	9.5	0.04	10.4	0.005	0.04				

148	7R54086	<0.1	0.29	4.3	28.0	0.10	0.09	0.03	11.1	114.5	14.65	1.26	1.3	<5	0.08	20.0	0.02	98	0.41	0.037	17.2	334.0	17.62	0.02	0.22	1.0	0.4	12.0	0.04	11.0	0.005	0.04	1.3	2	<0.1	49.1
149	7R54087	<0.1	0.24	5.5	30.5	0.14	0.03	0.03	8.1	117.5	16.99	1.09	1.0	<5	0.08	17.0	0.02	316	0.48	0.034	15.5	109.0	12.80	<0.02	0.24	0.8	0.3	9.0	0.02	8.3	0.005	0.04	1.2	2	<0.1	34.2

QC DATA:

Repeat:

1	7R53939	0.2	0.33	0.8	42.0	0.26	0.11	0.19	8.0	113.5	32.80	2.02	1.3	15	0.10	14.5	0.10	456	0.65	0.030	22.5	149.0	20.19	0.08	0.02	1.7	0.4	17.0	0.06	12.2	0.001	0.12	0.9	<2	<0.1	50.5
10	7R53948	0.1	0.71	4.4	59.5	0.50	0.21	0.03	11.2	98.0	27.72	2.59	2.7	5	0.12	17.5	0.44	436	0.73	0.032	23.8	250.0	21.89	0.16	0.02	2.0	0.4	30.0	0.06	15.3	0.002	0.10	3.0	2	<0.1	73.3
19	7R53957	0.1	0.39	3.5	36.0	0.28	0.54	0.04	5.8	120.0	9.91	1.49	1.6	25	0.07	18.0	0.24	434	0.32	0.042	11.9	166.0	16.45	0.08	0.06	2.0	0.4	71.0	0.08	17.2	0.003	0.06	1.5	<2	<0.1	32.2
36	7R53974	0.1	0.42	5.7	25.5	0.08	0.95	0.15	4.4	140.5	10.85	1.49	1.1	10	0.04	9.5	0.42	795	0.43	0.044	13.0	244.0	5.46	0.04	0.04	1.9	0.3	108.5	0.06	3.8	0.001	0.04	0.7	<2	<0.1	25.9
45	7R53983	0.2	1.11	8.7	67.5	0.22	0.26	0.08	15.9	43.0	46.57	4.53	3.0	50	0.11	38.5	0.80	671	0.30	0.039	47.9	661.0	16.54	0.18	0.08	2.4	0.8	40.0	0.06	14.2	0.001	0.08	2.0	6	<0.1	118.5
54	7R53992	0.1	0.61	8.9	78.0	0.22	0.94	0.23	12.9	101.5	27.68	2.60	2.5	35	0.09	34.0	0.53	884	0.71	0.037	32.1	471.0	17.89	0.20	0.10	2.2	0.7	84.5	0.10	12.3	0.002	0.08	1.2	<2	<0.1	52.2
71	7R54009	0.2	0.67	4.2	35.5	0.30	1.08	0.30	17.7	98.0	39.00	3.73	2.5	30	0.09	16.5	0.73	738	1.09	0.032	41.3	435.0	23.12	1.67	0.30	1.9	1.3	101.0	0.10	12.4	0.003	0.08	1.7	4	<0.1	71.1
80	7R54018	0.1	0.75	3.2	56.0	0.56	0.07	0.04	13.9	86.5	31.15	3.10	3.1	20	0.12	40.0	0.28	459	0.41	0.031	28.4	251.0	19.89	0.12	0.08	1.5	0.8	20.5	0.06	21.9	0.002	0.14	3.3	<2	<0.1	93.7
89	7R54027	0.1	0.76	1.9	34.0	0.30	0.06	0.04	6.0	102.0	12.96	1.98	2.3	30	0.06	27.5	0.14	439	0.24	0.028	15.5	219.0	16.12	<0.02	0.06	1.5	0.5	14.0	0.04	14.9	0.001	0.06	2.3	<2	<0.1	52.2
106	7R54044	<0.1	0.41	1.6	44.0	0.42	0.10	0.06	5.9	94.0	32.93	2.72	2.3	25	0.23	38.5	0.05	72	0.25	0.021	18.9	337.0	30.47	<0.02	0.18	0.9	0.5	15.0	0.04	14.7	0.001	0.08	1.0	4	<0.1	74.5
115	7R54053	0.1	0.79	2.7	37.5	0.46	0.14	0.15	14.2	84.0	34.62	2.74	2.6	20	0.24	18.5	0.37	352	0.50	0.023	32.2	259.0	28.40	0.56	0.06	1.0	0.3	16.0	0.04	12.9	0.001	0.08	2.0	6	<0.1	98.6
124	7R54062	0.1	0.95	2.8	41.5	0.38	0.14	0.05	11.7	89.5	32.35	3.13	3.3	25	0.24	36.5	0.28	362	0.36	0.025	23.5	244.0	24.09	<0.02	0.08	1.1	0.5	14.0	0.04	15.5	0.001	0.08	1.3	4	<0.1	78.6

Resplit:

1	7R53939	0.1	0.35	1.0	42.5	0.28	0.11	0.19	8.0	118.0	32.80	2.03	1.3	15	0.10	14.5	0.10	463	0.66	0.037	23.1	149.0	21.22	0.10	0.04	1.6	0.4	18.0	0.06	12.5	0.001	0.10	0.9	<2	<0.1	50.5
36	7R53974	0.1	0.44	7.3	27.0	0.10	1.01	0.18	5.5	146.0	13.00	1.57	1.4	15	0.04	11.5	0.45	836	0.53	0.046	15.5	257.0	6.79	0.02	0.06	2.1	0.3	115.0	0.06	4.4	0.002	0.04	0.9	<2	<0.1	28.1
71	7R54009	0.2	0.65	3.9	38.0	0.28	1.10	0.24	15.9	93.5	37.51	3.63	2.4	25	0.08	17.5	0.74	705	1.05	0.031	39.1	421.0	21.24	1.63	0.30	1.6	1.1	101.5	0.12	11.9	0.003	0.08	1.7	4	<0.1	66.3
106	7R54044	0.2	0.44	1.5	48.0	0.44	0.10	0.07	5.7	96.5	30.54	2.66	2.3	25	0.25	40.5	0.05	69	0.22	0.022	17.6	327.0	28.65	<0.02	0.16	1.0	0.6	15.5	0.04	14.7	0.001	0.08	1.1	4	<0.1	74.5
141	7R54079	0.2	0.28	8.5	39.0	0.44	0.05	0.06	8.2	125.5	23.52	2.35	1.4	10	0.10	21.0	0.03	299	0.71	0.041	17.3	168.0	29.30	0.02	0.24	1.6	0.3	17.5	0.08	10.6	0.005	0.04	0.8	4	<0.1	39.0

Standard:

PB113A	11.4	0.30	66.4	35.0	1.37	1.64	42.62	1.9	4.5	2237.00	1.01	1.4	80	0.03	2.5	0.12	1365	62.05	0.039	1.5	167.0	5424.00	0.91	9.66	0.8	0.2	98.5	0.10	0.8	0.034	0.20	0.2	8	0.4	7008.1
PB113A	11.9	0.29	66.5	35.0	1.38	1.59	43.31	1.7	4.0	2349.00	1.02	1.3	80	0.06	2.5	0.12	1500	62.43	0.032	1.3	169.0	5494.00	1.04	7.90	1.0	0.2	110.0	0.30	0.3	0.009	0.18	0.3	8	<0.1	7079.0
PB113A	11.9	0.30	64.5	39.0	1.38	1.56	44.34	1.7	4.0	2319.00	1.01	1.3	80	0.06	2.5	0.12	1492	62.69	0.033	1.3	164.0	5513.00	1.02	8.40	1.0	0.4	109.5	0.32	0.5	0.009	0.18	0.4	6	<0.1	7085.0
PB113A	11.8	0.28	65.6	45.0	1.18	1.65	48.55	2.1	5.0	2294.00	1.02	1.4	85	0.08	3.0	0.13	1554	66.52	0.032	1.7	180.0	5491.00	1.03	9.16	0.7	0.4	107.0	0.32	0.4	0.009	0.10	0.4	8	0.1	7059.0
PB113A	10.4	0.26	68.0	47.5	1.16	1.72	48.35	2.0	5.0	2314.00	1.02	1.4	80	0.08	3.0	0.13	1594	67.67	0.031	1.5	183.0	5524.00	1.10	9.20	1.0	0.4	102.5	0.28	0.4	0.007	0.08	0.3	8	<0.1	6994.0
PB113A	11.6	0.27	64.2	45.5	1.17	1.65	46.58	1.9	5.3	2332.50	1.07	1.3	80	0.07	2.5	0.11	1456	64.50	0.032	1.4	171.5	5561.45	1.11	7.67	0.8	0.4	107.3	0.28	0.3	0.008	0.09	0.3	9	<0.1	6984.3

ECO TECH LABORATORY LTD.
 Jutta Jealouse
 B.C. Certified Assayer

JJ/nl
 df/msr1563S/msr1806S
 XLS/07

CERTIFICATE OF ASSAY AW 2007-7513

Aurora Geosciences
34a Laberge Rd
Whitehorse, YT
Y1A 5Y9

17-Dec-07

No. of samples received: 136

Sample Type: Core

Project: CWG-7518-YT

Shipment #: 7

Submitted by: Kel Sax

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	7R53803	<0.03	<0.001
2	7R53804	0.03	0.001
3	7R53805	<0.03	<0.001
4	7R53806	<0.03	<0.001
5	7R53807	<0.03	<0.001
6	7R53808	<0.03	<0.001
7	7R53809	<0.03	<0.001
8	7R53810	0.05	0.001
9	7R53811	<0.03	<0.001
10	7R53812	<0.03	<0.001
11	7R53813	<0.03	<0.001
12	7R53814	<0.03	<0.001
13	7R53815	<0.03	<0.001
14	7R53816	<0.03	<0.001
15	7R53817	<0.03	<0.001
16	7R53818	<0.03	<0.001
17	7R53819	<0.03	<0.001
18	7R53820	<0.03	<0.001
19	7R53821	<0.03	<0.001
20	7R53822	<0.03	<0.001
21	7R53823	<0.03	<0.001
22	7R53824	<0.03	<0.001
23	7R53825	<0.03	<0.001
24	7R53826	<0.03	<0.001
25	7R53827	0.03	0.001
26	7R53828	<0.03	<0.001
27	7R53829	<0.03	<0.001
28	7R53830	0.03	0.001
29	7R53831	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse

B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	7R53832	<0.03	<0.001
31	7R53833	<0.03	<0.001
32	7R53834	<0.03	<0.001
33	7R53835	<0.03	<0.001
34	7R53836	<0.03	<0.001
35	7R53837	<0.03	<0.001
36	7R53838	<0.03	<0.001
37	7R53839	<0.03	<0.001
38	7R53840	<0.03	<0.001
39	7R53841	<0.03	<0.001
40	7R53842	<0.03	<0.001
41	7R53843	<0.03	<0.001
42	7R53844	<0.03	<0.001
43	7R53845	<0.03	<0.001
44	7R53846	<0.03	<0.001
45	7R53847	<0.03	<0.001
46	7R53848	<0.03	<0.001
47	7R53849	<0.03	<0.001
48	7R53850	<0.03	<0.001
49	7R53851	<0.03	<0.001
50	7R53852	<0.03	<0.001
51	7R53853	<0.03	<0.001
52	7R53854	<0.03	<0.001
53	7R53855	<0.03	<0.001
54	7R53856	<0.03	<0.001
55	7R53857	<0.03	<0.001
56	7R53858	<0.03	<0.001
57	7R53859	<0.03	<0.001
58	7R53860	<0.03	<0.001
59	7R53861	<0.03	<0.001
60	7R53862	<0.03	<0.001
61	7R53863	<0.03	<0.001
62	7R53864	<0.03	<0.001
63	7R53865	<0.03	<0.001
64	7R53866	<0.03	<0.001
65	7R53867	<0.03	<0.001
66	7R53868	<0.03	<0.001
67	7R53869	<0.03	<0.001
68	7R53870	<0.03	<0.001
69	7R53871	<0.03	<0.001
70	7R53872	<0.03	<0.001
71	7R53873	<0.03	<0.001
72	7R53874	<0.03	<0.001
73	7R53875	<0.03	<0.001

ECO TECH LABORATORY LTD.Jutta Jealous
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	7R53876	<0.03	<0.001
75	7R53877	<0.03	<0.001
76	7R53878	<0.03	<0.001
77	7R53879	<0.03	<0.001
78	7R53880	<0.03	<0.001
79	7R53881	<0.03	<0.001
80	7R53882	<0.03	<0.001
81	7R53883	<0.03	<0.001
82	7R53884	<0.03	<0.001
83	7R53885	<0.03	<0.001
84	7R53886	0.03	0.001
85	7R53887	<0.03	<0.001
86	7R53888	<0.03	<0.001
87	7R53889	<0.03	<0.001
88	7R53890	<0.03	<0.001
89	7R53891	<0.03	<0.001
90	7R53892	0.11	0.003
91	7R53893	<0.03	<0.001
92	7R53894	<0.03	<0.001
93	7R53895	<0.03	<0.001
94	7R53896	<0.03	<0.001
95	7R53897	<0.03	<0.001
96	7R53898	<0.03	<0.001
97	7R53899	<0.03	<0.001
98	7R53900	<0.03	<0.001
99	7R53901	<0.03	<0.001
100	7R53902	<0.03	<0.001
101	7R53903	<0.03	<0.001
102	7R53904	<0.03	<0.001
103	7R53905	<0.03	<0.001
104	7R53906	<0.03	<0.001
105	7R53907	<0.03	<0.001
106	7R53908	<0.03	<0.001
107	7R53909	<0.03	<0.001
108	7R53910	<0.03	<0.001
109	7R53911	<0.03	<0.001
110	7R53912	<0.03	<0.001
111	7R53913	0.03	0.001
112	7R53914	0.03	0.001
113	7R53915	<0.03	<0.001
114	7R53916	<0.03	<0.001
115	7R53917	<0.03	<0.001
116	7R53918	0.04	0.001
117	7R53919	<0.03	<0.001

ECO TECH LABORATORY LTD.Jutta Jealous
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
118	7R53920	<0.03	<0.001
119	7R53921	<0.03	<0.001
120	7R53922	<0.03	<0.001
121	7R53923	0.04	0.001
122	7R53924	<0.03	<0.001
123	7R53925	<0.03	<0.001
124	7R53926	<0.03	<0.001
125	7R53927	<0.03	<0.001
126	7R53928	0.03	0.001
127	7R53929	<0.03	<0.001
128	7R53930	<0.03	<0.001
129	7R53931	<0.03	<0.001
130	7R53932	<0.03	<0.001
131	7R53933	<0.03	<0.001
132	7R53934	<0.03	<0.001
133	7R53935	<0.03	<0.001
134	7R53936	<0.03	<0.001
135	7R53937	<0.03	<0.001
136	7R53938	<0.03	<0.001

QC DATA:**Repeat:**

		<0.03	<0.001
1	7R53803	<0.03	<0.001
10	7R53812	<0.03	<0.001
19	7R53821	<0.03	<0.001
36	7R53838	<0.03	<0.001
45	7R53847	<0.03	<0.001
54	7R53856	<0.03	<0.001
71	7R53873	<0.03	<0.001
80	7R53882	<0.03	<0.001
89	7R53891	<0.03	<0.001
106	7R53908	0.03	0.001
115	7R53917	<0.03	<0.001
124	7R53926	<0.03	<0.001
133	7R53935	<0.03	<0.001

Resplit:

1	7R53803	<0.03	<0.001
36	7R53838	<0.03	<0.001
71	7R53873	<0.03	<0.001
106	7R53908	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealous

B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
Standard:			
	OX154	1.82	0.053
	OX154	1.86	0.054
	OX154	1.84	0.054

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.
Jutta Jealouse
B.C. Certified Assayer

CERTIFICATE OF ASSAY AW 2007-7514

Aurora Geosciences
34a Laberge Rd
Whitehorse, YT
Y1A 5Y9

19-Dec-07

No. of samples received: 149
Sample Type: Core
Project: CWQ-7518-YT
Submitted by: Kel Sax

ET #.	Tag #	Au (g/t)	Au (oz/t)
1	7R53939	<0.03	<0.001
2	7R53940	<0.03	<0.001
3	7R53941	<0.03	<0.001
4	7R53942	<0.03	<0.001
5	7R53943	<0.03	<0.001
6	7R53944	<0.03	<0.001
7	7R53945	<0.03	<0.001
8	7R53946	<0.03	<0.001
9	7R53947	<0.03	<0.001
10	7R53948	<0.03	<0.001
11	7R53949	<0.03	<0.001
12	7R53950	<0.03	<0.001
13	7R53951	<0.03	<0.001
14	7R53952	<0.03	<0.001
15	7R53953	<0.03	<0.001
16	7R53954	<0.03	<0.001
17	7R53955	<0.03	<0.001
18	7R53956	<0.03	<0.001
19	7R53957	<0.03	<0.001
20	7R53958	<0.03	<0.001
21	7R53959	<0.03	<0.001
22	7R53960	<0.03	<0.001
23	7R53961	<0.03	<0.001
24	7R53962	<0.03	<0.001
25	7R53963	<0.03	<0.001
26	7R53964	<0.03	<0.001
27	7R53965	<0.03	<0.001
28	7R53966	<0.03	<0.001
29	7R53967	<0.03	<0.001

ECO TECH LABORATORY LTD.
Jutta Jealous
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
30	7R53968	<0.03	<0.001
31	7R53969	<0.03	<0.001
32	7R53970	<0.03	<0.001
33	7R53971	<0.03	<0.001
34	7R53972	<0.03	<0.001
35	7R53973	<0.03	<0.001
36	7R53974	<0.03	<0.001
37	7R53975	<0.03	<0.001
38	7R53976	<0.03	<0.001
39	7R53977	<0.03	<0.001
40	7R53978	<0.03	<0.001
41	7R53979	<0.03	<0.001
42	7R53980	<0.03	<0.001
43	7R53981	<0.03	<0.001
44	7R53982	<0.03	<0.001
45	7R53983	<0.03	<0.001
46	7R53984	<0.03	<0.001
47	7R53985	<0.03	<0.001
48	7R53986	<0.03	<0.001
49	7R53987	<0.03	<0.001
50	7R53988	<0.03	<0.001
51	7R53989	<0.03	<0.001
52	7R53990	<0.03	<0.001
53	7R53991	<0.03	<0.001
54	7R53992	<0.03	<0.001
55	7R53993	<0.03	<0.001
56	7R53994	0.04	0.001
57	7R53995	<0.03	<0.001
58	7R53996	<0.03	<0.001
59	7R53997	<0.03	<0.001
60	7R53998	<0.03	<0.001
61	7R53999	<0.03	<0.001
62	7R54000	<0.03	<0.001
63	7R54001	<0.03	<0.001
64	7R54002	0.03	0.001
65	7R54003	<0.03	<0.001
66	7R54004	<0.03	<0.001
67	7R54005	<0.03	<0.001
68	7R54006	<0.03	<0.001
69	7R54007	0.03	0.001
70	7R54008	0.03	0.001
71	7R54009	0.04	0.001
72	7R54010	<0.03	<0.001
73	7R54011	<0.03	<0.001

ECO TECH LABORATORY LTD.Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
74	7R54012	0.03	0.001
75	7R54013	0.04	0.001
76	7R54014	<0.03	<0.001
77	7R54015	<0.03	<0.001
78	7R54016	0.06	0.002
79	7R54017	<0.03	<0.001
80	7R54018	<0.03	<0.001
81	7R54019	<0.03	<0.001
82	7R54020	0.03	0.001
83	7R54021	<0.03	<0.001
84	7R54022	<0.03	<0.001
85	7R54023	<0.03	<0.001
86	7R54024	<0.03	<0.001
87	7R54025	<0.03	<0.001
88	7R54026	<0.03	<0.001
89	7R54027	<0.03	<0.001
90	7R54028	<0.03	<0.001
91	7R54029	<0.03	<0.001
92	7R54030	<0.03	<0.001
93	7R54031	<0.03	<0.001
94	7R54032	<0.03	<0.001
95	7R54033	<0.03	<0.001
96	7R54034	<0.03	<0.001
97	7R54035	<0.03	<0.001
98	7R54036	<0.03	<0.001
99	7R54037	<0.03	<0.001
100	7R54038	<0.03	<0.001
101	7R54039	0.04	0.001
102	7R54040	<0.03	<0.001
103	7R54041	<0.03	<0.001
104	7R54042	0.07	0.002
105	7R54043	<0.03	<0.001
106	7R54044	<0.03	<0.001
107	7R54045	<0.03	<0.001
108	7R54046	<0.03	<0.001
109	7R54047	<0.03	<0.001
110	7R54048	<0.03	<0.001
111	7R54049	<0.03	<0.001
112	7R54050	<0.03	<0.001
113	7R54051	<0.03	<0.001
114	7R54052	<0.03	<0.001
115	7R54053	<0.03	<0.001
116	7R54054	<0.03	<0.001
117	7R54055	<0.03	<0.001

ECO TECH LABORATORY LTD.Jutta Jealous
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
118	7R54056	<0.03	<0.001
119	7R54057	<0.03	<0.001
120	7R54058	<0.03	<0.001
121	7R54059	<0.03	<0.001
122	7R54060	<0.03	<0.001
123	7R54061	<0.03	<0.001
124	7R54062	<0.03	<0.001
125	7R54063	<0.03	<0.001
126	7R54064	<0.03	<0.001
127	7R54065	<0.03	<0.001
128	7R54066	<0.03	<0.001
129	7R54067	<0.03	<0.001
130	7R54068	<0.03	<0.001
131	7R54069	<0.03	<0.001
132	7R54070	<0.03	<0.001
133	7R54071	<0.03	<0.001
134	7R54072	<0.03	<0.001
135	7R54073	<0.03	<0.001
136	7R54074	<0.03	<0.001
137	7R54075	<0.03	<0.001
138	7R54076	<0.03	<0.001
139	7R54077	<0.03	<0.001
140	7R54078	<0.03	<0.001
141	7R54079	<0.03	<0.001
142	7R54080	<0.03	<0.001
143	7R54081	<0.03	<0.001
144	7R54082	<0.03	<0.001
145	7R54083	<0.03	<0.001
146	7R54084	<0.03	<0.001
147	7R54085	<0.03	<0.001
148	7R54086	<0.03	<0.001
149	7R54087	<0.03	<0.001

QC DATA:

Repeat:

10	7R53948	<0.03	<0.001
19	7R53957	<0.03	<0.001
36	7R53974	<0.03	<0.001
45	7R53983	<0.03	<0.001
54	7R53992	<0.03	<0.001
71	7R54009	<0.03	<0.001
80	7R54018	<0.03	<0.001

ECO TECH LABORATORY LTD.

Jutta Jealouse
B.C. Certified Assayer

ET #.	Tag #	Au (g/t)	Au (oz/t)
89	7R54027	<0.03	<0.001
106	7R54044	<0.03	<0.001
115	7R54053	<0.03	<0.001
124	7R54062	<0.03	<0.001
141	7R54079	<0.03	<0.001
Resplit:			
1	7R53939	<0.03	<0.001
36	7R53974	<0.03	<0.001
71	7R54009	<0.03	<0.001
106	7R54044	<0.03	<0.001
141	7R54079	<0.03	<0.001
Standard:			
OXi54		1.88	0.055
OXi54		1.84	0.054
OXi54		1.85	0.054
OXi54		1.86	0.054
OXi54		1.82	0.053

JJ/nl
XLS/07

ECO TECH LABORATORY LTD.

Jutta Jealous
B.C. Certified Assayer

Appendix IV

Analytical Procedure Assessment Report

Eco Tech Laboratory LTD is registered for ISO 9001-2000 by QMI Quality registrars (CDN 52172-01) for the "provision of assay and geochemical analytical services". EcoTech also Participates in the Canadian Certified Reference Materials Project (CCRMP) testing program annually.

SAMPLE PREPARATION

Samples are catalogued and logged into the sample-tracking database. During the logging in process, samples are checked for spillage and general sample integrity. It is verified that samples match the sample shipment requisition provided by the clients. The samples are transferred into a drying oven and dried.

Soils are prepared by sieving through an 80-mesh screen to obtain a minus 80-mesh fraction.

Samples unable to produce adequate minus 80-mesh material are screened at a coarser fraction. These samples are flagged with the relevant mesh.

Rock samples are 2 stage crushed on a Terminator jaw crusher to minus 10 mesh ensuring that 70% passes through a Tyler 10 mesh screen.

Every 35 samples a resplit is taken using a riffle splitter to be tested to ensure the homogeneity of the crushed material.

A 250 gram sub sample of the crushed material is pulverized on a ring mill pulverizer ensuring that 95% passes through a 150 mesh screen. The sub sample is rolled, homogenized and bagged in a pre-numbered bag.

A barren gravel blank is prepared after each job in the sample prep to be analyzed for trace contamination along with the actual samples.

ASSAY GOLD ANALYSIS

A 30 g sample size is fire assayed using appropriate fluxes. On each worksheet there is a repeat sample for every 10 samples, plus one re-split per run of 35 or under. The resultant dore bead is parted and then digested with aqua regia and then analyzed on a Perkin Elmer AA instrument. (Detection limit 0.03 g/t AA)

Appropriate standards and repeat/resplit samples (Quality Control Components) accompany the samples on the data sheet. Results are entered and printed along with quality control data (repeats, re-splits and standards).

ICP-MS ANALYSIS

Samples are digested in an aqua regia solution for 45 minutes. They are bulked to 10 ml with de-ionized water, and an aliquot of this is taken for analysis on the ICP-MS. All synthetic standards are purchased and verified by 3 independent analysts and are used for instrument calibration before each and every ICP-MS run.

A 2-3 point standardization curve is used to check the linearity (high and low). Certified reference material is used to check the performance of the machine and to ensure that proper digestion occurred in the wet lab. QC samples are run along with the client samples to ensure no machine drift or instrumentation issues occurred during the run procedure. Repeat samples (every 10 or less) and re-splits (every 35 or less) are also run to ensure proper weighing and digestion occurred.

Detection Limits:

Ag	0.02-100	Mo	0.01-2000
Al	0.01-10%	Na	0.001-10%
As	0.1-10000	Ni	0.1-10000
B	1-2000	P	0.001-5%
Ba	0.5-10000	Pb	0.01-10000
Bi	0.02-2000	S	0.02-10%
Ca	0.01-40%	Sb	0.02-2000
Cd	0.01-2000	Sc	0.1-100
Co	0.1-2000	Se	0.1-100
Cr	0.5-10000	Sr	0.5-10000
Cu	0.01-10000	Te	0.02-1000
Fe	0.01-40%	Th	0.1-2000
Ga	0.1-10000	Ti	0.001-10%
Hg	5-10000 ppb	Tl	0.02-1000
K	0.01-10%	U	0.1-2000
La	0.5-10000	V	2-10000
Mg	0.01-30%	W	0.1-100
Mn	1-10000	Zn	0.1-10000

units are in ppm, unless otherwise stated

Appendix V

SCHEDULE A

<u>Grant Number</u>	<u>Claim Name</u>	<u>Expiry Date</u>	<u>Renewal Requested</u>
YC20855	Bell 10	10/12/2011	0.25 yrs
YC20886	Bell 11	7/12/2008	4.50 yrs
YC20887	Bell 12	10/12/2011	0.25 yrs
YC20888	Bell 13	7/12/2008	4.50 yrs
YC20889	Bell 14	10/12/2011	0.25 yrs
YC20890	Bell 15	7/12/2008	4.50 yrs
YC20891	Bell 16	10/12/2011	0.25 yrs
YC20892	Bell 17	10/12/2011	0.25 yrs
YC20893	Bell 18	10/12/2011	0.25 yrs
YC20894	Bell 19	10/12/2011	0.25 yrs
YC20895	Bell 20	10/12/2011	0.25 yrs
YC20896	Bell 21	10/12/2011	0.25 yrs
YC20897	Bell 22	10/12/2011	0.25 yrs
YC20898	Bell 23	10/12/2011	0.25 yrs
YC20899	Bell 24	10/12/2011	0.25 yrs
YC21554	Blue 1	10/12/2011	0.25 yrs
YC21555	Blue 2	10/12/2011	0.25 yrs
YC21556	Blue 3	10/12/2011	0.25 yrs
YC21557	Blue 4	10/12/2011	0.25 yrs
YC28846	Wind 1	9/17/2013	3.25 yrs
YC28847	Wind 2	9/17/2013	3.25 yrs
YC28848	Wind 3	9/17/2013	3.25 yrs
YC28849	Zephyr 1	9/17/2013	3.25 yrs
YC28850	Zephyr 2	9/17/2013	3.25 yrs
YC28851	Zephyr 3	9/17/2013	3.25 yrs
YC28852	Storm 1	9/17/2013	3.25 yrs
YC28853	Storm 2	9/17/2013	3.25 yrs
YC28854	Storm 3	9/17/2013	3.25 yrs
YC28855	Gale 1	9/17/2013	3.25 yrs
YC28856	Gale 2	9/17/2013	3.25 yrs
YC28857	Gale 3	9/17/2013	3.25 yrs
YC34617	Breeze 1	9/13/2014	3.25 yrs
YC34618	Breeze 2	9/13/2014	3.25 yrs
YC34619	Breeze 3	9/13/2014	3.25 yrs
YC34620	Breeze 4	9/13/2014	3.25 yrs
YC34621	Breeze 5	9/13/2014	3.25 yrs
YC34622	Breeze 6	9/13/2014	3.25 yrs
YC34623	Breeze 7	9/13/2014	3.25 yrs
YC34624	Breeze 8	9/13/2014	3.25 yrs
YC35578	Blizzard 1	12/15/2012	4 yrs



YC35579	Blizzard 2	12/15/2013	4 yrs
YC35580	Blizzard 3	12/15/2012	4 yrs
YC35581	Blizzard 4	12/15/2013	4 yrs
YC35582	Blizzard 5	12/15/2012	4 yrs
YC35583	Blizzard 6	12/15/2013	4 yrs
YC35584	Blizzard 7	12/15/2012	4 yrs
YC35585	Blizzard 8	12/15/2012	4 yrs
YC35586	Blizzard 9	12/15/2013	4 yrs
YC35587	Blizzard 10	12/15/2013	4 yrs
YC35588	Blizzard 11	12/15/2013	4 yrs
YC35589	Blizzard 12	12/15/2013	4 yrs
YC35590	Blizzard 13	12/15/2013	4 yrs
YC35591	Blizzard 14	12/15/2012	4 yrs
YC35592	Blizzard 15	12/15/2013	4 yrs
YC35593	Blizzard 16	12/15/2012	4 yrs

YC36582	Squall 1	12/02/2007	5 yrs
YC36583	Squall 2	12/02/2007	5 yrs
YC36584	Squall 3	12/02/2007	5 yrs
YC36585	Squall 4	12/02/2007	5 yrs
YC36586	Squall 5	12/02/2007	5 yrs
YC36587	Squall 6	12/02/2008	4 yrs
YC36588	Squall 7	12/02/2007	5 yrs
YC36589	Squall 8	12/02/2008	4 yrs
YC36590	Squall 9	12/02/2007	5 yrs
YC36591	Squall 10	12/02/2007	5 yrs
YC36592	Squall 11	12/02/2007	5 yrs
YC36593	Squall 12	12/02/2007	5 yrs
YC36594	Squall 13	12/02/2007	5 yrs
YC36595	Squall 14	12/02/2007	5 yrs
YC36596	Squall 15	12/02/2007	5 yrs
YC36597	Squall 16	12/02/2007	5 yrs
YC36598	Squall 17	12/02/2007	5 yrs
YC36599	Squall 18	12/02/2007	5 yrs
YC36600	Squall 19	12/02/2007	5 yrs
YC36601	Squall 20	12/02/2007	5 yrs
YC36602	Squall 21	12/02/2007	5 yrs
YC36603	Squall 22	12/02/2007	5 yrs
YC36604	Squall 23	12/02/2007	5 yrs
YC36605	Squall 24	12/02/2007	5 yrs
YC36606	Squall 25	12/02/2007	5 yrs
YC36607	Squall 26	12/02/2007	5 yrs
YC36608	Squall 27	12/02/2007	5 yrs
YC36609	Squall 28	12/02/2007	5 yrs
YC36610	Squall 29	12/02/2007	5 yrs
YC36611	Squall 30	12/02/2008	4 yrs
YC36612	Squall 31	12/02/2007	5 yrs
YC36613	Squall 32	12/02/2008	4 yrs
YC36614	Squall 33	12/02/2007	5 yrs
YC36615	Squall 34	12/02/2009	4 yrs
YC36616	Squall 35	12/02/2008	4 yrs
YC36617	Squall 36	12/02/2008	4 yrs

YC36618	Squall 37	12/02/2007	5 yrs
YC36619	Squall 38	12/02/2007	5 yrs
YC36620	Squall 39	12/02/2007	5 yrs
YC36621	Squall 40	12/02/2007	5 yrs
YC36622	Squall 41	12/02/2007	5 yrs
YC36623	Squall 42	12/02/2007	5 yrs
YC36624	Squall 43	12/02/2008	4 yrs
YC36625	Squall 44	12/02/2007	5 yrs
YC36626	Squall 45	12/02/2008	4 yrs
YC36627	Squall 46	12/02/2007	5 yrs
YC36628	Squall 47	12/02/2008	4 yrs
YC36629	Squall 48	12/02/2007	5 yrs
YC36630	Squall 49	12/02/2008	4 yrs
YC36631	Squall 50	12/02/2007	5 yrs
YC36632	Squall 51	12/02/2008	4 yrs
YC36633	Squall 52	12/02/2007	5 yrs
YC36634	Squall 53	12/02/2007	5 yrs
YC36635	Squall 54	12/02/2007	5 yrs
YC36636	Squall 55	12/02/2007	5 yrs
YC36637	Squall 56	12/02/2007	5 yrs
YC36638	Squall 57	12/02/2007	5 yrs
YC36639	Squall 58	12/02/2007	5 yrs
YC36640	Squall 59	12/02/2008	4 yrs
YC36641	Squall 60	12/02/2008	4 yrs
YC36642	Squall 61	12/02/2008	4 yrs
YC36643	Squall 62	12/02/2008	4 yrs

117 Claims

464.5 years



CURLEW LAKE RESOURCES LTD.
CLEAR CREEK PROPERTY
2007 EXPLORATION PROGRAM
Property Compilation Map

NTS: 1:15P14
 Datum: NAD83
 Job: CWQ-7518-YT

District: Dawson, YT
 Projection: UTM Zone 8N
 Date: 15 MARCH 08

AURORA GEOSCIENCES LTD.