



Certificate of Analysis

Work Order: VC122087

To: Kendra Johnston
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA STREET
VACOUVER BC V6B 4N8

Date: Sep 21, 2012

P.O. No. : PO#: GZ-90403-05/YK022-GZ
Project No. : -
No. Of Samples : 74
Date Submitted : Aug 20, 2012
Report Comprises : Pages 1 to 9
(Inclusive of Cover Sheet)

Distribution of unused material:

Active files - upstairs:

Certified By :

Satpal Gill
QAQC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method

M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Methods marked with an asterisk (e.g. *NAA08V) were subcontracted

Methods marked with the @ symbol (e.g. @AAS21E) denote accredited tests

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element	WtKg	Au	Ag	Al	As	Be	Ca	Ba	Bi	Cd
Method	WGH79	FAA313	ICP14B							
Det.Lim.	0.001	5	2	0.01	3	0.5	0.01	5	5	1
Units	kg	ppb	ppm	%	ppm	ppm	%	ppm	ppm	ppm
L838325	0.300	5	<2	1.98	9	<0.5	0.14	145	<5	<1
L838326	0.315	<5	<2	1.56	4	<0.5	0.13	130	<5	<1
L838327	0.175	<5	<2	1.57	4	<0.5	0.09	145	<5	<1
L838328	0.255	<5	<2	1.89	9	0.5	0.09	180	<5	<1
L838329	0.280	<5	<2	1.48	6	<0.5	0.06	65	<5	<1
L838330	0.200	<5	<2	2.22	8	<0.5	0.10	150	<5	1
L838331	0.200	<5	<2	2.22	12	0.7	0.40	254	<5	<1
L838332	0.190	<5	<2	1.80	6	<0.5	0.54	337	<5	1
L838333	0.245	<5	<2	2.25	5	0.6	0.41	292	<5	<1
L838334	0.280	7	<2	2.29	<3	0.7	0.10	236	<5	<1
L838335	0.300	<5	<2	2.57	7	<0.5	0.12	178	<5	<1
L838336	0.240	<5	<2	1.28	11	<0.5	0.14	196	<5	<1
L838337	0.260	<5	<2	2.05	11	<0.5	0.14	238	<5	<1
L838338	0.175	<5	<2	1.45	<3	<0.5	0.13	200	<5	<1
L838339	0.165	<5	<2	1.89	5	<0.5	0.19	318	<5	<1
L838340	0.235	<5	<2	2.09	5	<0.5	0.39	434	<5	<1
L838341	0.185	<5	<2	2.11	7	<0.5	0.17	190	<5	<1
L838342	0.230	<5	<2	1.97	5	<0.5	0.25	262	<5	<1
L838343	0.335	<5	<2	1.54	4	<0.5	0.18	192	<5	<1
L838344	0.270	<5	<2	2.34	11	0.5	0.13	257	<5	<1
L838345	0.275	<5	<2	2.20	9	0.5	0.14	301	<5	<1
L838346	0.285	<5	<2	1.62	6	0.5	0.25	258	<5	<1
L838347	0.270	<5	<2	1.31	<3	0.6	0.25	510	<5	<1
L838348	0.395	<5	<2	1.84	3	0.6	0.62	342	<5	<1
L838349	0.195	<5	<2	1.54	10	0.9	0.89	482	<5	1
L838350	0.130	5	<2	1.49	10	1.0	0.98	531	<5	<1
L838351	0.325	<5	<2	1.93	<3	0.7	0.50	515	<5	<1
L838352	0.355	<5	<2	2.75	3	0.5	0.49	539	<5	1
L838353	0.340	<5	<2	1.72	5	<0.5	0.21	232	<5	<1
L838354	0.380	<5	<2	1.87	9	<0.5	0.28	291	<5	<1
L838355	0.285	<5	<2	1.29	4	<0.5	0.21	262	<5	<1
L838356	0.330	<5	<2	2.32	<3	<0.5	0.43	425	<5	<1
L838357	0.340	<5	<2	3.52	<3	0.7	0.69	627	<5	<1
L838358	0.295	<5	<2	1.48	<3	<0.5	0.28	311	<5	<1
L838359	0.275	<5	<2	2.45	<3	<0.5	0.46	460	<5	<1
L838360	0.295	<5	<2	1.97	7	<0.5	0.15	148	<5	<1
L838361	0.420	<5	<2	1.47	4	<0.5	0.18	175	<5	<1
L838362	0.275	<5	<2	1.67	<3	<0.5	0.32	214	<5	<1
L838363	0.280	<5	<2	1.97	4	0.6	0.45	261	<5	<1
L838364	0.300	<5	<2	1.94	3	<0.5	0.27	294	<5	<1
L838365	0.330	<5	<2	1.91	4	0.7	0.43	288	<5	<1
L838366	0.370	<5	<2	1.79	7	0.5	0.29	280	<5	<1
L838367	0.315	<5	<2	1.65	6	<0.5	0.12	170	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	WtKg WGH79	Au FAA313	Ag ICP14B	Al ICP14B	As ICP14B	Be ICP14B	Ca ICP14B	Ba ICP14B	Bi ICP14B	Cd ICP14B
L838368	0.300	<5	<2	1.86	4	<0.5	0.16	175	<5	<1
L838369	0.320	6	<2	2.27	10	0.6	0.12	233	<5	<1
L838370	0.330	<5	<2	2.14	7	0.5	0.15	409	<5	<1
L838371	0.325	<5	<2	1.68	8	<0.5	0.18	244	<5	<1
L838372	0.345	<5	<2	1.66	6	<0.5	0.18	290	<5	<1
L838373	0.395	<5	<2	2.43	8	0.7	0.22	280	<5	<1
L838374	0.355	<5	<2	1.70	<3	<0.5	0.29	338	<5	<1
L838375	0.330	<5	<2	1.75	<3	<0.5	0.30	395	<5	<1
L838376	0.360	5	<2	1.92	7	0.5	0.23	351	<5	<1
L838377	0.335	<5	<2	2.27	6	0.6	0.45	630	<5	<1
L838378	0.340	<5	<2	1.38	5	<0.5	0.24	270	<5	<1
L838379	0.290	<5	<2	1.88	7	<0.5	0.18	273	<5	<1
L838380	0.380	<5	<2	1.62	<3	<0.5	0.26	446	<5	<1
L838381	0.320	<5	<2	1.48	6	<0.5	0.21	287	<5	<1
L838382	0.355	<5	<2	1.98	5	<0.5	0.17	244	<5	<1
L838383	0.335	<5	<2	1.46	<3	<0.5	0.16	191	<5	<1
L838384	0.335	<5	<2	1.60	5	<0.5	0.14	342	<5	<1
L838385	0.365	<5	<2	1.86	5	0.5	0.25	410	<5	<1
L838386	0.345	<5	<2	2.28	7	0.5	0.17	395	<5	<1
L838387	0.440	<5	<2	2.18	3	<0.5	0.26	293	<5	<1
L838388	0.295	<5	<2	1.68	3	0.5	0.23	334	<5	<1
L838389	0.295	<5	<2	1.64	5	<0.5	0.37	393	<5	<1
L838390	0.405	7	<2	2.10	3	0.7	0.55	331	<5	<1
L838391	0.365	<5	<2	1.71	4	0.5	0.37	334	<5	<1
L838392	0.365	<5	<2	1.79	6	0.5	0.29	379	<5	<1
L838393	0.375	<5	<2	1.90	5	<0.5	0.33	155	<5	<1
L838394	0.360	7	<2	1.55	4	<0.5	0.40	354	<5	<1
L838395	0.365	<5	<2	2.00	7	<0.5	0.20	283	<5	<1
L838396	0.325	<5	<2	1.63	3	<0.5	0.33	286	<5	<1
L838397	0.397	<5	<2	2.98	4	0.7	0.80	152	<5	<1
L838398	0.315	<5	<2	1.73	4	<0.5	0.26	200	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B <1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L838325	9	30	17.1	2.56	<1	0.05	11.8	14	0.68	295
L838326	7	24	10.7	2.20	<1	0.03	9.1	11	0.59	251
L838327	6	26	14.9	2.31	<1	0.03	9.9	9	0.34	224
L838328	8	33	20.8	2.96	<1	0.04	10.9	13	0.48	263
L838329	7	12	3.3	1.36	<1	0.04	7.2	14	1.14	347
L838330	9	34	13.9	3.74	<1	0.04	11.1	19	0.57	265
L838331	11	45	15.3	2.87	<1	0.04	15.1	22	0.79	651
L838332	8	30	19.5	2.51	<1	0.04	11.1	11	0.60	787
L838333	10	33	20.5	3.18	<1	0.04	15.5	15	0.71	756
L838334	11	39	26.0	3.10	<1	0.05	10.1	13	0.51	339
L838335	12	35	23.9	3.29	<1	0.06	8.9	19	0.86	276
L838336	5	22	8.8	2.35	<1	0.06	7.7	8	0.33	186
L838337	8	37	16.1	3.27	<1	0.05	9.2	18	0.58	239
L838338	5	22	7.9	2.61	<1	0.04	9.2	9	0.35	170
L838339	8	28	8.9	2.76	<1	0.04	9.2	11	0.45	329
L838340	8	22	8.0	2.57	<1	0.11	7.9	9	0.48	779
L838341	7	32	11.0	3.00	<1	0.05	9.3	12	0.48	233
L838342	9	29	10.3	2.77	<1	0.08	10.1	11	0.48	508
L838343	6	27	8.8	2.55	<1	0.04	9.6	10	0.39	168
L838344	8	32	12.4	3.15	<1	0.05	11.0	13	0.50	217
L838345	10	33	13.2	3.09	<1	0.05	9.1	13	0.52	281
L838346	8	29	16.8	2.61	<1	0.05	13.1	10	0.44	207
L838347	4	13	10.0	1.93	<1	0.22	22.2	4	0.40	142
L838348	9	24	13.3	2.45	<1	0.07	13.7	10	0.55	280
L838349	11	20	29.4	3.07	<1	0.07	29.1	7	0.40	401
L838350	14	20	28.9	3.22	<1	0.07	32.4	6	0.37	493
L838351	10	23	11.0	2.99	<1	0.25	10.3	8	0.54	1250
L838352	13	25	8.1	4.00	<1	0.38	9.5	16	1.31	848
L838353	9	28	11.4	2.72	<1	0.17	10.5	10	0.50	272
L838354	11	31	20.0	2.96	<1	0.15	10.0	12	0.62	370
L838355	10	24	12.7	2.23	<1	0.09	8.7	8	0.48	375
L838356	15	25	17.3	3.27	<1	0.31	8.9	14	1.52	850
L838357	14	17	5.3	3.68	<1	0.30	6.7	19	2.00	748
L838358	13	27	11.2	2.50	<1	0.15	11.0	10	0.64	984
L838359	16	31	12.5	3.22	<1	0.30	8.1	19	1.54	908
L838360	11	26	27.2	3.02	<1	0.09	8.8	19	0.82	278
L838361	8	25	9.4	2.66	<1	0.12	11.4	11	0.54	226
L838362	9	28	21.5	2.30	<1	0.07	11.2	8	0.43	406
L838363	10	33	14.9	2.90	<1	0.04	10.7	10	0.56	587
L838364	9	33	11.7	2.59	<1	0.04	11.2	10	0.47	521
L838365	10	35	20.5	2.77	<1	0.05	15.0	10	0.64	499
L838366	9	32	13.3	2.59	<1	0.05	11.9	10	0.53	414
L838367	8	31	9.6	2.57	<1	0.06	7.9	12	0.59	257

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L838368	10	25	83.2	2.78	<1	0.09	8.9	16	0.87	248
L838369	11	36	19.4	3.33	<1	0.07	10.8	17	0.56	254
L838370	10	36	18.2	3.17	<1	0.08	9.4	14	0.62	319
L838371	9	28	11.7	2.99	<1	0.12	8.3	14	0.60	277
L838372	9	30	11.3	2.96	<1	0.13	9.0	13	0.69	430
L838373	13	32	20.3	3.64	<1	0.18	10.9	18	0.79	816
L838374	10	25	18.6	2.81	<1	0.13	7.9	14	0.91	432
L838375	12	22	8.6	2.73	<1	0.13	8.4	13	0.91	632
L838376	9	33	14.3	3.06	<1	0.16	13.8	12	0.76	338
L838377	16	20	6.9	3.15	<1	0.23	19.6	13	1.05	1310
L838378	8	22	8.4	2.42	<1	0.14	9.3	10	0.62	335
L838379	11	28	9.2	2.92	<1	0.08	8.5	11	0.77	359
L838380	9	13	3.2	2.53	<1	0.17	5.8	8	0.69	694
L838381	9	25	9.9	2.55	<1	0.11	9.4	10	0.53	511
L838382	11	31	20.1	3.19	<1	0.12	9.3	14	0.57	309
L838383	8	20	6.7	2.81	<1	0.09	7.8	12	0.56	294
L838384	8	25	10.3	2.74	<1	0.08	9.3	12	0.63	426
L838385	12	28	22.2	3.03	<1	0.13	8.6	12	0.81	581
L838386	12	28	15.8	3.51	<1	0.13	8.8	13	0.93	478
L838387	12	30	25.9	3.13	<1	0.09	7.7	13	0.86	278
L838388	10	30	10.0	2.69	<1	0.09	10.0	9	0.43	529
L838389	7	27	8.5	2.58	<1	0.07	10.4	9	0.52	468
L838390	10	28	11.9	3.23	<1	0.20	12.7	11	0.66	630
L838391	9	30	13.4	2.71	<1	0.10	10.8	9	0.47	469
L838392	9	29	10.3	2.67	<1	0.09	10.9	9	0.45	541
L838393	6	25	7.5	2.52	<1	0.07	10.1	9	0.44	190
L838394	8	26	12.0	2.44	<1	0.07	10.8	9	0.48	600
L838395	8	29	8.6	2.83	<1	0.05	9.1	10	0.47	360
L838396	8	25	17.1	2.60	<1	0.05	11.9	11	0.50	317
L838397	12	16	6.4	4.30	<1	0.07	8.3	14	0.82	453
L838398	6	22	7.8	2.59	<1	0.05	8.6	11	0.49	223

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L838325	<1	0.02	16	0.02	9	<0.01	<5	3.7	<10	14.7
L838326	<1	0.02	13	0.02	7	<0.01	<5	2.9	<10	12.4
L838327	1	0.02	12	0.07	13	<0.01	<5	2.6	<10	10.7
L838328	<1	0.02	18	0.03	10	<0.01	<5	3.2	<10	9.0
L838329	<1	0.02	8	0.02	6	<0.01	<5	1.9	<10	12.0
L838330	<1	0.02	18	0.03	14	<0.01	<5	3.2	<10	10.8
L838331	<1	0.02	27	0.02	16	<0.01	<5	6.1	<10	19.5
L838332	<1	0.02	20	0.03	21	0.01	<5	3.4	<10	20.5
L838333	<1	0.03	23	0.03	10	<0.01	<5	5.1	<10	22.1
L838334	<1	0.02	26	0.04	9	<0.01	<5	4.0	<10	10.5
L838335	<1	0.02	23	0.03	8	<0.01	<5	3.6	<10	15.2
L838336	<1	0.02	11	0.04	8	<0.01	<5	1.9	<10	13.9
L838337	<1	0.02	19	0.05	8	<0.01	<5	2.5	<10	14.7
L838338	<1	0.02	12	0.02	8	<0.01	<5	2.0	<10	12.9
L838339	<1	0.02	16	0.03	10	<0.01	<5	2.3	<10	22.6
L838340	<1	0.02	14	0.07	7	0.01	<5	2.1	<10	44.9
L838341	<1	0.02	17	0.04	10	<0.01	<5	2.7	<10	23.4
L838342	<1	0.02	17	0.03	6	<0.01	<5	2.8	<10	26.9
L838343	<1	0.02	14	0.03	8	<0.01	<5	2.3	<10	19.0
L838344	<1	0.02	19	0.03	8	<0.01	<5	3.1	<10	18.9
L838345	<1	0.02	21	0.03	7	<0.01	<5	2.5	<10	23.1
L838346	<1	0.02	19	0.04	7	<0.01	<5	4.0	<10	26.4
L838347	<1	0.02	5	0.04	6	<0.01	<5	3.6	<10	65.6
L838348	<1	0.03	16	0.08	5	<0.01	<5	4.6	<10	65.9
L838349	<1	0.03	18	0.14	5	0.06	<5	3.6	<10	103
L838350	<1	0.03	19	0.16	6	0.08	<5	4.0	<10	118
L838351	<1	0.02	14	0.05	5	<0.01	<5	5.5	<10	52.6
L838352	<1	0.02	15	0.08	3	<0.01	<5	8.5	<10	49.4
L838353	<1	0.02	16	0.03	6	<0.01	<5	3.2	<10	20.0
L838354	<1	0.02	21	0.03	10	<0.01	<5	4.5	<10	30.0
L838355	<1	0.02	13	0.03	7	<0.01	<5	2.8	<10	20.6
L838356	<1	0.02	15	0.06	5	<0.01	<5	7.2	<10	36.8
L838357	<1	0.02	13	0.13	7	<0.01	<5	7.3	<10	73.5
L838358	<1	0.02	17	0.02	6	<0.01	<5	4.3	<10	23.6
L838359	<1	0.02	17	0.06	6	<0.01	<5	5.4	<10	43.8
L838360	<1	0.02	17	0.05	8	<0.01	<5	4.1	<10	20.8
L838361	<1	0.02	13	0.01	8	<0.01	<5	3.6	<10	13.8
L838362	<1	0.02	14	0.01	12	<0.01	<5	4.9	<10	13.1
L838363	<1	0.03	20	0.01	9	<0.01	<5	5.2	<10	20.2
L838364	<1	0.02	18	0.02	11	<0.01	<5	4.5	<10	15.5
L838365	<1	0.02	22	0.02	9	<0.01	<5	5.8	<10	17.3
L838366	<1	0.02	19	0.01	10	<0.01	<5	4.4	<10	15.7
L838367	<1	0.02	18	0.03	6	<0.01	<5	2.5	<10	11.8

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L838368	<1	0.02	16	0.04	5	<0.01	<5	4.2	<10	15.1
L838369	<1	0.02	22	0.03	10	<0.01	<5	3.2	<10	12.5
L838370	<1	0.02	25	0.05	10	<0.01	<5	2.9	<10	16.6
L838371	<1	0.02	18	0.03	8	<0.01	<5	2.8	<10	18.0
L838372	<1	0.02	20	0.07	8	<0.01	<5	3.2	<10	14.7
L838373	<1	0.02	23	0.16	6	<0.01	<5	3.6	<10	18.7
L838374	<1	0.02	16	0.07	7	<0.01	<5	3.0	<10	23.1
L838375	<1	0.02	16	0.07	6	<0.01	<5	3.5	<10	24.2
L838376	<1	0.02	23	0.04	8	<0.01	<5	4.7	<10	26.8
L838377	<1	0.02	15	0.09	5	<0.01	<5	7.4	<10	58.1
L838378	<1	0.02	16	0.03	8	<0.01	<5	2.9	<10	22.9
L838379	<1	0.02	17	0.04	5	<0.01	<5	3.1	<10	19.4
L838380	<1	0.02	7	0.02	4	<0.01	<5	3.1	<10	23.9
L838381	<1	0.02	16	0.03	4	<0.01	<5	2.6	<10	22.0
L838382	<1	0.02	21	0.05	9	<0.01	<5	3.0	<10	17.0
L838383	<1	0.02	12	0.04	7	<0.01	<5	2.9	<10	16.3
L838384	<1	0.02	15	0.02	6	<0.01	<5	2.9	<10	14.7
L838385	<1	0.02	18	0.04	4	<0.01	<5	4.1	<10	22.7
L838386	<1	0.02	18	0.06	6	<0.01	<5	5.1	<10	17.6
L838387	<1	0.02	17	0.05	9	<0.01	<5	3.4	<10	24.2
L838388	<1	0.02	18	0.06	8	<0.01	<5	4.1	<10	20.7
L838389	<1	0.02	15	0.03	6	<0.01	<5	3.4	<10	68.3
L838390	<1	0.03	18	0.08	10	<0.01	<5	5.3	<10	52.0
L838391	<1	0.02	20	0.04	9	<0.01	<5	4.9	<10	30.9
L838392	<1	0.02	17	0.06	8	<0.01	<5	4.3	<10	28.5
L838393	<1	0.02	12	0.05	3	<0.01	<5	2.7	<10	38.4
L838394	<1	0.02	17	0.05	6	<0.01	<5	4.3	<10	33.6
L838395	<1	0.02	14	0.04	7	<0.01	<5	2.7	<10	20.0
L838396	<1	0.02	16	0.05	7	<0.01	<5	3.8	<10	32.4
L838397	<1	0.03	9	0.17	5	<0.01	<5	3.1	<10	69.0
L838398	<1	0.02	13	0.05	5	<0.01	<5	2.3	<10	28.7

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L838325	0.10	58	<10	3.4	50	3.1
L838326	0.09	59	<10	2.7	41	1.6
L838327	0.07	56	<10	3.2	36	1.4
L838328	0.08	77	<10	3.4	43	1.9
L838329	0.10	43	<10	2.7	61	1.0
L838330	0.09	69	<10	2.5	42	5.7
L838331	0.08	75	<10	9.2	50	5.9
L838332	0.06	57	<10	5.5	49	2.3
L838333	0.07	66	<10	9.4	52	4.0
L838334	0.08	68	<10	2.8	48	3.7
L838335	0.11	76	<10	1.9	47	2.6
L838336	0.07	61	<10	1.6	34	2.8
L838337	0.08	76	<10	1.8	38	1.5
L838338	0.08	61	<10	1.6	41	2.5
L838339	0.08	65	<10	1.6	57	3.4
L838340	0.09	58	<10	1.7	75	1.1
L838341	0.08	70	<10	1.7	65	3.7
L838342	0.07	62	<10	2.0	53	1.8
L838343	0.07	60	<10	1.7	40	3.2
L838344	0.09	74	<10	2.0	62	6.0
L838345	0.09	70	<10	1.6	57	4.0
L838346	0.07	57	<10	4.8	38	3.9
L838347	0.16	52	<10	6.6	34	1.2
L838348	0.12	67	<10	5.9	50	3.0
L838349	0.06	62	<10	11.6	33	1.4
L838350	0.06	58	<10	13.6	31	1.7
L838351	0.12	63	<10	4.8	56	4.6
L838352	0.26	105	<10	4.1	95	5.1
L838353	0.10	58	<10	2.1	48	1.9
L838354	0.11	69	<10	2.9	51	5.0
L838355	0.08	56	<10	2.0	44	1.3
L838356	0.19	81	<10	3.2	84	2.8
L838357	0.23	88	<10	4.6	135	2.7
L838358	0.11	61	<10	3.6	50	2.9
L838359	0.22	95	<10	2.0	106	2.2
L838360	0.13	84	<10	2.2	52	4.2
L838361	0.10	57	<10	2.8	36	5.5
L838362	0.04	56	<10	4.4	30	5.8
L838363	0.08	66	<10	3.8	44	8.6
L838364	0.06	63	<10	3.2	39	5.3
L838365	0.07	62	<10	9.6	44	7.3
L838366	0.08	60	<10	3.4	42	9.0
L838367	0.10	69	<10	1.5	42	5.3

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L838368	0.12	77	<10	2.2	44	2.3
L838369	0.10	70	<10	2.3	43	3.8
L838370	0.09	67	<10	1.9	48	5.8
L838371	0.11	70	<10	1.9	47	4.9
L838372	0.11	70	<10	2.1	59	4.9
L838373	0.12	73	<10	2.6	68	3.1
L838374	0.11	76	<10	1.5	61	2.4
L838375	0.12	63	<10	1.9	64	2.1
L838376	0.12	64	<10	3.3	57	4.6
L838377	0.17	77	<10	6.3	98	2.7
L838378	0.10	54	<10	2.2	41	1.7
L838379	0.12	69	<10	1.7	49	2.5
L838380	0.04	50	<10	1.8	54	1.6
L838381	0.09	56	<10	1.8	46	2.7
L838382	0.10	66	<10	2.3	48	5.0
L838383	0.11	67	<10	1.7	54	2.6
L838384	0.09	62	<10	1.7	52	2.3
L838385	0.12	76	<10	2.0	74	4.0
L838386	0.14	86	<10	1.9	100	2.9
L838387	0.14	81	<10	1.7	79	2.1
L838388	0.07	58	<10	2.7	55	4.4
L838389	0.07	59	<10	2.7	50	1.8
L838390	0.13	68	<10	4.9	66	5.8
L838391	0.08	58	<10	3.1	50	5.6
L838392	0.07	61	<10	2.7	54	3.3
L838393	0.07	58	<10	1.8	51	1.4
L838394	0.08	52	<10	4.2	42	6.1
L838395	0.08	66	<10	1.7	61	2.5
L838396	0.07	56	<10	4.5	42	1.3
L838397	0.18	104	<10	3.8	90	2.6
L838398	0.08	57	<10	1.9	40	2.3

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.