
**Geochemical, Geophysical, and RAB Drilling Survey
Assessment Report:
GT Probe, Soil Sampling, IP Survey, & RAB Drilling**

QV PROJECT

Volume I - Report

Claims:

QV 1-10	YC61008-017
QV 11-24	YC88221-8234
QV 25-72	YD13837-884
QV 73-188	YD13885-14000
QV 189-288	YD48801-48900
QV 289-342	YD47943-996
QV 343-494	YE21103-254
QV 495-524	YE76847-876
QV 525-714	YF03605 -794
QV 715-791	YF76235 -311
QV 792-822	YF00412-442

Dawson Mining District

NTS: 1150/05

Latitude: 63.16.2° N Longitude: -139.32.8 ° W

Soil Sampling Performed On: July 21-22 & 28-29, 2016

IP Survey Performed On: July 13 – 18 & 21 – 25, 2016

GT Probe Performed On: July 9 – 29, 2016

RAB Drilling Performed On: August 27 – November 9, 2016

Prepared for Comstock Metals Ltd.

By GroundTruth Exploration

Written by: Jodie Gibson, P.Geo. & Adam Fage, P.Geo.

August 19, 2017

Table of Contents

INTRODUCTION5

1 PROPERTY DESCRIPTION.....5

2 CLAIM INFORMATION7

3 HISTORY9

4 GEOLOGY11

4.1 REGIONAL GEOLOGY11

4.2 PROPERTY GEOLOGY14

4.3 MINERALIZATION17

5 2016 QV EXPLORATION PROGRAM AND RESULTS18

5.1 DC IP-RESISTIVITY SURVEYS18

5.2 GT PROBE.....24

5.3 SOIL SAMPLING.....29

5.4 RAB DRILLING32

5.5 SAMPLE PREPARATION, LABORATORY ANALYSIS, AND QA/QC.....42

6 INTERPRETATION AND RECOMMENDATIONS43

6.1 VG ZONE.....44

6.2 KORAT – TETRA AREA.....48

6.3 STEWART AREA49

6.4 SHADOW AREA51

6.5 ESTIMATED BUDGET52

7 COSTS53

8 REFERENCES.....55

9 STATEMENTS OF QUALIFICATION.....56

APPENDIX A: IP RESISTIVITY PROFILES58

APPENDIX B: SOIL SAMPLES ASSAY CERTIFICATE.....59

APPENDIX C: GT PROBE SAMPLES ASSAY CERTIFICATE.....60

APPENDIX D: RAB DRILLING SAMPLES61

APPENDIX E: RAB ASSAY CERTIFICATES62

Table of Figures

Figure 1 – QV Property location map.	6
Figure 2 – QV Property claim map. Area outlined in red are claims staked in 2016 (QV 792 – 822).	8
Figure 3 – VG Zone Mineral Resource Estimate Table from Paulter & Shankar (2014).	11
Figure 4 – QV Property regional geology.	13
Figure 5 – QV property geology (from Paulter & Shankar 2014).	16
Figure 6 – VG Zone geology (from Cooley & Leatherman 2013b).	17
Figure 7 – Supersting DC IP-Resistivity system.	19
Figure 8 - 2016 DC IP-Resistivity Lines on the VG Zone (QVIP33 – 38 in pink).	20
Figure 9 – 2013 Resistivity section QVIP-03 showing correlation between gold in diamond drilling and resistivity low features on the VG.	21
Figure 10 – 2016 Resistivity section from line QVIP-38; looking SW. Highlights strong resistivity low on trend of known mineralization at the VG Zone that warrants follow up drill testing.	22
Figure 11 - 2016 DC IP-Resistivity Lines on the Shadow Zone (QVIP39 – 44 in pink).	23
Figure 12 – 2016 Resistivity section from line QVIP16-41 showing subvertical break in the resistivity data.	24
Figure 13 – GT Probe.	25
Figure 14 – Gold in 2016 GT Probe samples on the VG Zone.	26
Figure 15 – Molybdenum in 2016 GT Probe samples on the VG Zone.	27
Figure 16 – Gold in GT Probe samples from the Shadow Zone.	28
Figure 17 – Gold in GT Probe samples from the Stewart zone.	29
Figure 18 – Gold in soils on the Shadow Zone showing 2016 sample locations.	31
Figure 19 – Gold in soils on the Stewart zone showing 2016 sample locations.	32
Figure 20 – GT RAB Drill on the QV Property; drill hole 16QVVRAB-03.	33
Figure 21 - 2016 VG Zone RAB Plan.	35
Figure 22 - Cross-section of drill holes QV13-12, 16QVV017, & 16QVV-18 with resistivity.	38
Figure 23 - 2016 Shadow Zone RAB Plan with gridded gold in soils and IP-Resistivity lines.	40
Figure 24 - Stewart Zone 2016 RAB Plan with gridded gold in soils and GT Probe sampling.	42
Figure 25 - Plan map of the VG Zone with historic and proposed drilling and the modelled surface trace of the VG Zone (red dotted line), the VG footwall zone (orange dotted line),	

and the Telegraph Fault. The blue lies represent a series of sections from Leapfrog presented in following Figures 26 – 28..... 45

Figure 26 - Cross-section along drill holes QV13-012, 16QVV017, & 16QVV018 showing interpreted surface of mineralization (red plane) and interpolated grade shells (red = > 1g/t Au, orange = >0.5 g/t Au). 46

Figure 27 - Oblique view of 200m wide long section of the VG Zone showing proposed western drill holes and estimated interception with the model VG zone surface (red). . 46

Figure 28 - Oblique view of 200m wide cross section of the eastern VG Zone showing proposed eastern drill holes and estimated interception with the model VG zone surface (red)..... 47

Figure 29 - Proposed infill soil grids on the VG Zone. 48

Figure 30 - Proposed infill soil grid in the Korat-Tetra area with TMI airborne magnetics and gold in soils from Northern Tiger. 49

Figure 31 - Proposed infill soil grid on the Stewart Zone with Mo in soils over gridded Au in soils. 50

Figure 32 - Proposed grid soils in the Shadow area with Mo in soils over gridded gold in soils. 51

Table of Tables

Table 1 - 2017 VG Zone RAB Collars 34

Table 2 - Summary of Assays from 2017 RAB Drilling on the VG Zone..... 39

Table 3 - 2017 Shadow Zone Drill Collars..... 40

Table 4 - Summary of Assays from 2017 RAB Drilling on the Shadow Zone. 41

Table 5 - 2017 Stewart Zone RAB Collars 41

Table 6 - Summary of Assays from 2017 RAB Drilling on the Stewart Zone..... 42

Introduction

A comprehensive work program including DC IP-Resistivity surveys, GT Probe sampling, soil sampling, and RAB drilling was conducted on the QV property (“Property”) between July 9th – November 15th, 2016. The work was focused in three target areas: the VG Zone, the Stewart Zone, and the Shadow Zone. The purpose of the work was to 1.) better assess the potential for near surface alteration and mineralization along strike of the VG zone to the east and west; 2.) assess, at a broad scale, the footprint of alteration/mineralization beneath permafrost at the Stewart Zone; and 3.) expand IP and geochemical coverage along the Spirit Fault in the Shadow Zone. Ultimately, the work was designed to provide a framework for a Phase 2 program of 2,423m of RAB drilling over 34 holes that was conducted on the VG, Shadow, and Stewart Zones in September – November of 2016. Additionally, 33 quartz claims were staked in the central portion of the property to infill an internal gap of lapsed claims surrounding the Korat claims.

Ground Truth Exploration Inc. (“Ground Truth”) of Dawson City, Yukon to performed the 2016 work on Comstock Metals Ltd. Behalf. A total of 360 GT Probe samples were collected over 12 lines on the VG, Stewart, and Shadow zones; 5.04 line-km of high resolution IP-Resistivity surveys were performed on the VG & Shadow Targets; 451 soil samples were collected on the Stewart and Shadow zones; and 2,423m of RAB drilling over 34 holes that was conducted on the VG, Shadow, and Stewart Zones. The results and interpretation of these surveys form the basis of this report.

1 Property Description

The Property is in the Yukon’s White Gold district, approximately 80 km South of Dawson, YT within the Dawson Mining District on NTS mapsheet 115O/05 at Latitude 63° 16.2’ N and Longitude 139° 32.8’ W.

The Property can be reached via helicopter from Dawson City, YT. There is road access through the Klondike Goldfields to the junction of Henderson and North Henderson Creeks’ that can serve as a helicopter staging zone; approximately 15km to the North East.

Gold is the primary commodity of interest on the property, and the most significant work to date has focused on the VG Zone. The VG Zone hosts structurally-controlled, gold mineralization, with strong similarities to Kinross’ Golden Saddle Deposit; 10km south.




Figure 1 – QV Property location map.

2 Claim Information

The QV Project is registered in the Dawson Mining district on mapsheet 115O/3-6. (Figure 2). It encompasses 16,335 hectares and is composed of the following 824 claims:

Claim name	Grant Number	Owner	Operator
QV 1-10	YC61008-017	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 11-24	YC88221-8234	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 25-72	YD13837-884	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 73-188	YD13885-14000	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 189-288	YD48801-48900	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 289-342	YD47943-996	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 343-494	YE21103-254	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 495-524	YE76847-876	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 525-714	YF03605 -794	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 715-791	YF76235 -311	Comstock Metals Ltd - 100%	Comstock Metals Ltd
QV 792-822	YF00412 – 442	Comstock Metals Ltd - 100%	Comstock Metals Ltd




Figure 2 – QV Property claim map. Area outlined in red are claims staked in 2016 (QV 792 – 822).

3 History

(excerpts from Jean Pautler, P.Geo. and Ali Shahkar, P.Eng. 43-101 Technical Report on the QV Project dated August 20, 2014)

Claims including the North Star and Black Diamond were staked on a bluff above the Yukon River in 1901 by J. McGillivray and C.J. Hahneman, who drove a 4.6m adit later that year (Deklerk, 2010, Minfile 115O 010). The claims, documented under the Treva Minfile occurrence (Minfile 115O 010), probably related to Ogilvie's report of an 1887 rumour that an extensive gold bearing quartz vein had been found on the west side of the Yukon River, 2 miles (3.2 km) south of the Stewart River (Department of the Interior, 1889). The adit (Figure 2) was located at 576290mE, 7016305mN in the fall of 2012, driven on quartz veins at the base of a bluff on the QV property, along the Yukon River. No significant gold results were obtained from the adit, but anomalous arsenic (maximum 1465 ppm) and antimony (maximum 14 ppm) are evident, suggestive of the signature of the VG zone within metasedimentary host rocks, and the surrounding area, which exhibits alteration, has not been explored.

There is no subsequent work reported until staking of the initial QV 1-10 claims by Shawn Ryan in 2007. A 62 sample soil geochemical survey was conducted by RyanWood Exploration Inc. for Shawn Ryan in 2008 (Ryan, 2008). The soil survey outlined spotty anomalous gold values up to 20.6 ppb Au, 1.09 ppm Hg (with adjacent anomalous arsenic, antimony and nickel) flanking the same aeromagnetic high, similar to the original geochemical and magnetic signature closely associated with gold mineralization on the White Gold Project (White claims), which now hosts the Golden Saddle deposit of Kinross Gold Corporation, 11 km to the south.

Additional QV claims were staked in 2009 to 2013. Comstock Metals Ltd. optioned the claims from Shawn Ryan in June, 2010, largely based on the similar geochemical and geophysical signatures and proximity to the Golden Saddle deposit.

Exploration by Comstock Metals Ltd. since acquisition in 2010 consisted of the collection of 8,161 ridge and spur and grid soil samples, prospecting and geological mapping with coincident geochemical sampling, a 773 line kilometre airborne magnetic and radiometric geophysical survey, ground magnetic surveys and 32 induced polarization lines over the VG, Stewart and Shadow zones, 3,570m of small excavator trenching in 28 trenches, 3,005m of direct push and geoprobe sampling on the QV, Stewart and Shadow grids, an aerial drone survey over the VG zone, and 3,419m of diamond drilling in 17 holes on the VG zone.

Visible gold was initially discovered on the southern QV Project by Comstock Metals Ltd. on June 10, 2012 while conducting follow up prospecting of a gold in soil anomaly; an initial grab sample returned 16.28 g/t Au and 47 g/t Ag with anomalous bismuth, tellurium, mercury, molybdenum and lead. The VG zone consists of quartz \pm carbonate veins, stockwork and breccia zones, as well as pyrite veinlets, including cubic pyrite and visible gold, associated with intense-quartz-carbonate-sericite (or possible illite) alteration, with albite, pervasive K-spar and hematite. Overall gold is associated with anomalous silver, mercury, bismuth, tellurium, molybdenum, antimony, and barium. This style of mineralization and alteration is analogous to that at the Golden Saddle deposit on the White Gold Project.

Trenching on the VG zone in 2012 delineated a 450m by 65m, 250° trending zone of gold mineralization.

- Trench results (reported as length along the trench, not true widths) include:
 - o 3.52 g/t Au over 80m from QVTR12-6,
 - o 1.63 g/t Au over 95m from QVTR12-12, and
 - o 2.18 g/t Au over 85m from QVTR12-13.
- Drilling on the VG zone intersected true widths of
 - o 2.23 g/t Au over 42m in QV12-004,
 - o 1.45 g/t Au over 60m in DDH QV12-6,
 - o 1.03 g/t Au over 78m in DDH QV12-1, including 6.15 g/t Au over 5.6m,
 - o 1.36 g/t Au over 42.6m in DDH QV13-11 (275m down dip of the mineralized zone in the discovery trench, QVTR12-6), and
 - o 1.76 g/t Au over 42.3m in DDH QV13-12 (at the open ended western limit of the zone).

The drill program delineated an open ended 250°/20-30°N trending, near surface tabular body of gold mineralization at the VG zone with a strike extent of 325m, traced up to 275m down dip from surface, and averaging 35-40m true thickness. Mineralization remains open to the west, down dip and beneath the mafic hornblende gneiss to the east and

further exploration and infill drilling is recommended. The most favourable drill orientation is 160°/-60 to -70°.

A 43-101 compliant, independent resource estimate was performed on the VG Zone by Ali Shankar, P. Eng. of Lions Gate Geological Consulting Inc., Sechelt, B.C. The resource was effective as of June 30th, 2014 and reports an Inferred resource of 4,390,000 Tonnes at an average grade of 1.65 g/t Au for a total of 230,000 ounces gold at the VG Zone.

Table 1 VG Zone Inferred Mineral Resource Estimate Reported using a 0.5 g/t gold cut-off grade

<i>Deposit</i>	<i>Category</i>	<i>Tonnes</i>	<i>Gold Grade (g/t)</i>	<i>Contained Gold (ounces)</i>
VG	Inferred	4,390,000	1.65	230,000

Notes to accompany Mineral Resource table

1. The Qualified Person responsible for the estimate is Ali Shahkar, P.Eng., of LGGC.
2. The assumed mining method is open pit mining.
3. Reported Mineral Resources are constrained by an open pit shell using a gold price of US\$1300/ounce, mining cost of US\$2/tonne, process and general administration cost of US\$20/tonne, and a gold recovery of 94% (based on the neighbouring Golden Saddle deposit).
4. Mineral Resources are reported as undiluted.

Figure 3 – VG Zone Mineral Resource Estimate Table from Pautler & Shankar (2014).

4 Geology

4.1 Regional Geology

The QV Regional and Property geology is summarized below from Jean Pautler, P.Geo. and Ali Shahkar, P.Eng. 43-101 Technical Report on the QV Project dated August 20, 2014.

The QV Project occurs within the unglaciated Yukon Plateau portion of the Paleozoic Yukon-Tanana terrane, southwest of the Tintina and northeast of the Denali faults, dominated in the regional area by Devonian to Mississippian (and possibly older) metasiliciclastic rocks (DMps), which interfinger with, and are stratigraphically overlain by hornblende bearing schists and gneisses and amphibolite (intermediate to mafic metavolcanic rocks) (DMa). The metasiliciclastic rocks include metamorphosed fine clastic rocks, quartzite and conglomerate. The above lithologies include marble horizons (DMc) and are metamorphosed to amphibolite grade. Devonian to Mississippian metasedimentary rocks (quartzite and metapelite) of the Nasina Assemblage (DMq) lie structurally above and/or may partly be equivalent to the above metaclastic unit.

Abundant orthogneiss bodies of Devonian to Mississippian (DMog - undivided, DMogg, DMoga, DMogt, DMogta) and Permian ages (Pog - undivided, Pogg, Poga), with compositions ranging from granite (g) to K-spar augen bearing (a), to tonalite and diorite (t), occur within Yukon-Tanana Terrane. DMogta represents undivided DMogt and DMA. Narrow bodies of Paleozoic ultramafic rocks (mPum), commonly serpentized (mPums), also occur within the area.

The above units are interpreted to represent two arcs, an older Devonian to Mississippian arc consisting of predominantly amphibolite (DMA) and associated subvolcanic intrusions (DMogg, DMoga, DMogt) built on a siliciclastic basement (DMps, DMq, DMcg, DMNq) and a Permian arc of granitic orthogneiss (Pogg, Poga) and coeval metavolcanic rocks (PKs) built on the Devonian-Mississippian arc.

The above lithologies are intruded by plutons and stocks of early Jurassic aged granodiorite, and quartz monzonite (eJgd) and unconformably overlain by massive andesite flows and breccias of the Late Cretaceous Carmacks Group (uKv), locally with Early Cretaceous coarse clastic sedimentary rocks at the base of the sequence (IKs). Eocene feldspar +-quartz porphyry dykes intrude the above (Er).




Figure 4 – QV Property regional geology.

4.2 Property Geology

Only limited property scale mapping (summarized in Figure 4) has been undertaken on the QV property, but regional (1:250,000) scale government mapping was completed through the area in 2005 and a compilation of the White Gold district was completed by the Mineral Deposit Research Unit, University of British Columbia (MDRU) in 2011 (Figure 3). A 3 by 3 km and adjoining 1 by 2.5 km area on the southern QV property (QV grid), incorporating the VG zone, was mapped at a 1:10,000 scale, with 1:5,000 detail of the VG zone, by Leatherman and Cooley (2013) and Cooley and Leatherman (2013b) (Figure 5), a preliminary 1.5 by 2.5 km area over the Stewart zone was mapped at a 1:20,000 scale by Cooley and Leatherman (2013a). Minor reconnaissance prospecting/mapping in gold in soil anomalous areas was completed by Ms. Pautler. The detailed geology and reconnaissance mapping has been integrated with the government geology in Figure 4. Detailed geology of the QV grid, and the VG and Shadow zones are summarized from Cooley and Leatherman, Leatherman and Cooley (2013) and Leatherman (2013), respectively.

Outcrop is limited on the property, generally confined to bluffs along the Yukon River. Exposure on the remaining property area is less than 1%, and generally restricted to south facing, bare to poplar vegetated hillsides, ridge tops and creek exposures.

The southern, eastern and western property areas are primarily underlain by Devonian to Mississippian (and possibly older) metasedimentary rocks (DMps), which interfinger with, and are stratigraphically overlain by, intermediate to mafic amphibolite (DMA) and hornblende gneiss (metamorphosed intermediate to mafic volcanic rocks) and minor felsic metavolcanic rocks (DMf). Marble horizons (Mb), commonly altered to calc-silicate and occasionally skarn due to regional metamorphism, locally occur at the contact between the metavolcanic and metasedimentary units; the latter include micaceous quartzite ± graphitic, biotite schist and muscovite schist.

A mafic (tonalitic) orthogneiss (DMogt) has been observed in the southeastern property area and may underlie the central property area. Granitic orthogneiss is shown to underlie the northwest property area and minor exposures were noted in the Shadow zone. Felsic feldspar augen gneiss of probable Permian age occurs within the VG and Shadow zones, but may be more extensive than mapped due to poor exposure. An ultramafic lense (mPums) is exposed along the bluffs above the Yukon River east of the VG zone (Figure 5) and just west of the property on Shamrock Dome (Figure 4). These are interpreted to occur along thrust faults.

The above units are intruded by an Early Jurassic granodiorite intrusion (EJgd), which is exposed in the eastern property area, and intrusions of probable Jurassic age underlie the Stewart, Tetra and Shadow zones.

Coarse grained crowded potassium feldspar syenite porphyry sills, with apparent zoned feldspars, and quartz eye granite dykes and sills intrude the Devonian (\pm older) to Mississippian package but are pre-mineralization. They have been observed in the southern QV area and at the Shadow zone. Age may be Early Jurassic and related to the intrusion in the eastern property area, similar to the Jual and Ten stocks further north (dated as Jurassic), or Permian A persistent mafic dyke probably of the Upper Cretaceous Carmacks Group has been mapped west of the VG and Shadow zones. Minor late fine grained, quartz \pm feldspar porphyry dykes of probable Eocene age (Er) are evident in the northern property area, including at the Tetra and Shadow zones.

The VG zone is underlain by an east-northeast dipping package of primarily felsic gneiss, commonly interlayered with biotite schist and less common mafic gneiss. The section appears to consist of a lower sequence of metamorphosed felsic volcanic rocks with minor mafic intervals, overlain by a thick mafic and intermediate volcanic rock unit which is in turn overlain by a thin limestone, followed by abundant interbedded sandstone and shale with locally high organic content. The section does not appear to be overturned (as suggested by the average foliation dipping more steeply than the lithological contact measured in cross sections). Average foliations for the VG area trend $343^{\circ}/53^{\circ}\text{NE}$ and lithology contacts at $332^{\circ}/33^{\circ}\text{NE}$. (Figure 5: Cooley & Leatherman, 2013)




Figure 5 – QV property geology (from Paulter & Shankar 2014).




Figure 6 – VG Zone geology (from Cooley & Leatherman 2013b).

4.3 Mineralization

Mineralization of QV Property, VG Zone

(from Jean Pautler, P.Geo. and Ali Shahkar, P.Eng. 43-101 Technical Report on the QV Project dated August 20, 2014)

Mineralization at the VG zone occurs as stacked or en-echelon lenses hosted along west-southwest, gently north-northwest dipping sheared zones (average orientation of 250°/20°N), which are common throughout the southern part of the QV property. The shear zones occur as one or more stacked and intersecting horizons. Subsequent brittle reactivation of these shallowly north-northwest dipping structures has included local fracturing of the adjacent felsic rocks, which has permitted the flow of hydrothermal fluid that caused sericite (illite) - pyrite alteration of the adjacent wallrock, and local gold mineralization. The primary host rock is biotite-feldspar(±augen)-quartz gneiss, which

occurs structurally below a hornblende-biotite-feldspar-quartz gneiss; the latter constitutes a distinct marker horizon identified by stubby hornblende crystals and anomalous chromium. Mineralized ore shoots may be parallel to the intersection lineation of S1 and S2, which is oriented at 347°/10°NE. The intersections of foliations (343°/53°NE) and lithological contacts (332°/33°NE) with the mineralizing structures (250°/20°N) may also control ore shoots.

The original soil anomaly over the VG zone on the QV grid consisted of a 2 km long (with a 500m gap through the hornblende gneiss unit) and up to 400m wide >10 ppb gold anomaly with maximum values of 395.6 ppb Au and 8.7 ppm Ag from a south facing slope, with better soil development than most of the property area. Infill soil sampling returned a maximum of 1277 ppb Au. At the VG zone and overall on the QV property anomalous gold in soils is associated with anomalous mercury, bismuth, tellurium, molybdenum, moderately high barium, antimony ±lead soil geochemistry.

5 2016 QV Exploration Program and Results

A comprehensive work program including DC IP-Resistivity surveys, GT Probe sampling, and soil sampling was conducted on the QV property (“Property”) between July 9th – 29th, 2016. The work was focused in three target areas: the VG Zone, the Stewart Zone, and the Shadow Zone. The purpose of the work was to 1.) better assess the potential for near surface alteration and mineralization along strike of the VG zone to the east and west; 2.) assess, at a broad scale, the footprint of alteration/mineralization beneath permafrost at the Stewart Zone; and 3.) expand IP and geochemical coverage along the Spirit Fault in the Shadow Zone. Ultimately, the work was designed to provide a framework for follow-up RAB drilling on the property conducted from August 27th – November 9th, 2016.

A total of 360 GT Probe samples were collected over 12 lines on the VG, Stewart, and Shadow zones; 5.04 line-km of high resolution IP-Resistivity surveys were performed on the VG & Shadow Targets; and 451 soil samples were collected on the Stewart and Shadow zones. The follow up RAB program consisted of 2,423m of drilling over 34 holes on the VG, Shadow, and Stewart zones. Details of the surveys and results are summarized in the follow sections.

5.1 DC IP-Resistivity Surveys

A total of 5.04 line-km of high resolution DC IP-Resistivity surveys over 13 lines were conducted on the VG (6 lines) and Shadow (7 lines) zones. The work was conducted using a 5-person crew utilizing the following Ground Truth Exploration personnel:

1. Jennifer Hanlon Foreman
2. Luke Severinsen Assistant
3. Norbert Kapa Helper
4. Patrick Dunbar Helper
5. Kendra Franks Helper

The DC Resistivity/IP System utilized was a Supersting R8, manufactured by Advanced Geosciences Inc. of Austin Texas. The output power of the system is 200w and it is powered by deep cycle batteries. It is an 8 channel system which allows up to 8 readings to be measured at the same time, typically up to 1000 readings can be read in 40 minutes. The system allows for multiple arrays to be read successively. The Res/IP surveys consisted of 84 electrodes at 5m spacing. Resistivity and chargeability sections for each survey are in Appendix A.



Figure 7 – Supersting DC IP-Resistivity system.

VG Zone

A total of 6 lines were surveyed on the VG Zone in 2016 (Figure 8). Eighteen additional lines were placed on the VG Zone during previous exploration efforts in 2012/13 and the 2016 survey was designed to extend the survey footprint to the E-NE along the trace of the Telegraph fault (lines 33 – 35) and extend the coverage from some historic survey lines to the SE (lines 36 – 38) and cover additional areas with gold in soil anomalies.

The 2016 surveys highlighted several resistivity low features to both the NE and SW of the current resource area that, based on previous surveys and diamond drilling, are potentially related to gold mineralization (Figure 2 & 3). Zones of mineralization within drill holes at the VG are consistently related with resistivity low features. These are interpreted to be highlighting the broader zones of sericite – clay (illite) alteration associated with gold mineralization in the area. Additionally, survey lines 34 – 36 (and historic line 24) highlight the apparent trace of the Telegraph fault to the NE




Figure 8 - 2016 DC IP-Resistivity Lines on the VG Zone (QVIP33 – 38 in pink).




Figure 9 – 2013 Resistivity section QVIP-03 showing correlation between gold in diamond drilling and resistivity low features on the VG.




Figure 10 – 2016 Resistivity section from line QVIP-38; looking SW. Highlights strong resistivity low on trend of known mineralization at the VG Zone that warrants follow up drill testing.

Shadow Zone

A total of 7 lines were surveyed on the Shadow Zone in 2016 (Figure 11). Six additional lines were placed over two areas, approximately 1km apart, over a NW-SE oriented trend on the Shadow Zone during previous exploration efforts in 2013. The 2016 survey was designed to extended the survey footprint to the SE (lines 39 – 40) and infill between the two previously surveyed areas (lines 41 – 45). Of particular interest, is the SE portion of the trend which consisted of a distinct, subvertical, break in resistivity data on historic lines 21 – 23 traceable for 235m along strike that is coincident with a linear, NW-SW trending, gold in soil anomaly.

The 2016 survey lines extended the resistivity break at the SE end of the Shadow Zone approximately 210m to the SE (LINES 39-40) and approximately 310m to the NW (lines 41, 42, & 45). The resistivity break is interpreted as a WNW trending fault (Spirit Fault) with an apparent steep dip to the NE (Figure 12). The structure has been traced for approximately 980m along strike in IP-Resistivity sections and is open to the NW and SE. Given the association of the interpreted structure with anomalous gold in soils the area is considered a priority target for follow up work.




Figure 11 - 2016 DC IP-Resistivity Lines on the Shadow Zone (QVIP39 – 44 in pink).




Figure 12 – 2016 Resistivity section from line QVIP16-41 showing subvertical break in the resistivity data.

5.2 GT Probe

A total of 360 GT Probe samples were collected over 12 lines on the VG, Stewart, and Shadow zones in 2016. The 2016 GT Probe program was conducted on July 10 – August 1, 2016 using a 3 person crew of the following GroundTruth Exploration personnel:

1. Phil Severiensen GT Probe Operator
2. Robin Miller GT Probe Assistant
3. Daniel Frost GT Probe Sampler

The GT Probe a direct push sampling rig mounted on low ground pressure rubber tracks. The rig is driven between sampling sites via wireless remote control and the operator drives a 3 ½” cased sampling rod to the bedrock interface and pulls up the sample. The Direct push drill is a Geoprobe® MT 540 which has been fitted onto the ground mobile platform designed by Tao Henderson of GroundTruth Exploration Inc.

As the GT Probe sampling rig is ground mobile and on light rubber tracks that significantly reduce ground disturbance, the method is a vast improvement over trenching for bedrock interface mineralization with respect to environmental concerns and is also more

productive (~50-75 m/day trenching production vs ~200 m/day GT Probe sampling at 5m spacing). Additionally, the work is classified as Mining Land Use class one activity, and the activities are non-invasive so no reclamation is necessary



Figure 13 – GT Probe

VG Zone

A total of 208 GT Probe samples were collected over 7 lines on the VG Zone and were designed to test the potential eastern and western extensions of the currently known mineralization in the area. The three eastern lines are designed to cross and projected trace of the Telegraph fault and mapped thrust faults in the area by Cooley and Leatherman (2013) in addition to gold in soil anomalies in the area. The western lines are designed to test the western extent of the system, following up on spotty, but anomalous gold in soil values in the area.

Assay values for the samples ranged from trace to 2.36 g/t Au. Anomalous gold (>0.1 g/t) in the samples from the area are coincident with elevated Mo (>3 ppm) +/- As-Pb-Sb-Te. This is a similar geochemical fingerprint observed with mineralization in drill holes from the area, however, Mo appears to be the most significant correlation with strongly elevated gold values (>1 g/t). Two significant anomalies were noted in the GT Probe sampling. The first consists of a 150m run of samples along a SW oriented ridge immediately south of the deposit area with sample values ranging from 0.067 – 2.36 g/t Au. The trend overlaps with a zone of strongly anomalous gold in soils (>50ppb) and rock chips from the probe samples consist dominantly of strongly sericite altered and oxidized felsic orthogneiss. Quartz veinlets and relict oxidized cubic pyrite is common. The second area occurs immediately SW of the resource area along the interpreted trace of

the Telegraph Fault and consists of the 36m, N-S oriented, run of samples ranging from 0.229 – 2.18 g/t Au. The samples overlap with a SW extension of the VG soil anomaly, all be it weaker (>10 ppb Au) and also corresponds to strongly sericite altered orthogneiss with quartz veinlets and relict oxidized pyrite.

There are also additional, smaller (1-2 sample), anomalies. These include a one hit sample 290m to the NE of the deposit area that returned 1.36 g/t Au within altered amphibolite and no associated gold in soil anomalies, and a 30m section of samples along the northern end of the eastern most line with lower level gold values (0.06 – 0.211 g/t Au) and anomalous Mo (8.9 – 11.6 ppm Mo).




Figure 14 – Gold in 2016 GT Probe samples on the VG Zone.




Figure 15 – Molybdenum in 2016 GT Probe samples on the VG Zone.

Shadow Zone

A total of 36 GT Probe samples were collected over 2 lines on the Shadow. A total of 5 GT Probe lines were originally planned but had to be abandoned due to mechanical issues with the probe. The lines completed crossed gold in soil anomalous along an NW-SE oriented ridge above the Spirit Fault. The samples only returned weak values for gold, ranging from trace to 0.357 g/t Au, with localised samples of anomalous As (up to 189 ppm) and Pb (up to 358 ppm). Rock chips from the GT Probe samples consisted dominantly of potassium feldspar rich orthogneiss with disseminated cubic pyrite and localised quartz veinlets.




Figure 16 – Gold in GT Probe samples from the Shadow Zone.

Stewart Zone

Three GT Probe lines for a total of 116 samples were completed along the 1.5km, E-W trending, Stewart Zone. The lines are wide spaced, approximately 300m apart, and were designed to cross gold in soil anomalies in the area. Previous trenching in the Stewart zone was challenged by strong permafrost in the area and the GT Probe program was designed to get a broad overview of the bedrock geochemistry that could be followed-up with additional lines and/or RAB drilling pending the results.

The samples return from trace to 0.262 g/t Au, with all significantly anomalous values (>0.1 g/t) within the central and eastern lines. Anomalous Mo (up to 17.9 ppm) and Pb (up to 189.2 ppm) also occur but are adjacent to the areas of anomalous gold.

It is currently unclear what is controlling the anomalies in the Stewart area, however, based on the GT Probe chips the anomalous gold samples and associated gold in soil anomaly occur immediately north of the contact with amphibolite (south) and a felsic gneiss (north). This implies either a lithologic and/or structural control in the area. Paulter & Shakhar (2014) also reports altered quartz-feldspar porphyry dikes from trenches in the area that may also be associated with mineralization.




Figure 17 – Gold in GT Probe samples from the Stewart zone.

5.3 Soil Sampling

A total of 451 soil samples were collected on the Stewart and Shadow Zones in 2016 using a 5-person crew that utilized the same Ground Truth staff that operated the DC IP-Resistivity surveys discussed above. The soil sampling is completed in the field according to the following procedure:

All sampling traverses are pre-planned, with pre -specified sampling intervals, typically 50m. Field technicians navigate to sample site using handheld GPS units. The soil sampler arrives at each sample site, identifies the most appropriate location to collect the sample and lays out a sheet of plastic (12"x20" ore bag). The soil sample is taken using an Eijklcamp brand hand auger at a depth of between 20cm and 110cm. Samplers strive to consistently collect C-Horizon sample material. Where necessary (rocky or frozen ground) a prospector's pick ('mattock') is used to obtain the sample.

The soil is laid out on the sheet of plastic in the order it was recovered from the sample hole. Two Standardized photos are taken at each sample site- 1) Sample Location photo: across slope, 5m from sample hole with auger inserted and 2) Sample Profile photo: Close up of sample laid out on ore bag with barcode tag and munsell color chart in photo.

The sampler places the necessary amount of soil (400-500 grams) from the bottom of the hole into a kraft sample bag. The bag labeled with the 3-letter project and tagged with a plastic barcode ID tag containing a unique 7 digit sample identification number is inserted. A plastic barcode ID tag with the sample identification number is attached to a rock or branch in a visible area at the sample site along with a length of pink flagging tape.

A field duplicate sample is taken once for every 25 samples. Both samples are given unique Sample identification number. The data for both samples is recorded and a note is made indicating the duplicate and its corresponding sample identification number. At client's discretion, standard reference material is inserted into the sample stream at an interval of 1:50.

The GPS location of the sample site is recorded with a Garmin GPSMap 60cx or 76cx GPS device in UTM NAD 83 format, and the waypoint is labeled with the project name and the sample identification number. A weather-proof handheld device equipped with a barcode scanner is used in the field to record the descriptive attributes of the sample collected. This includes: sample identification number (scanned into device at sample site), soil colour, soil horizon, slope, sample depth, ground and tree vegetation and sample quality and any other relevant information. As well, the GPS coordinates are entered into the handheld device as a secondary backup in case of GPS failure.

Shadow Zone

A total of 245 soil samples were collected from the Shadow Zone. The soils were designed as infill lines (50m spaced lines x 25m spaced samples) to tighten the soil coverage within the central portion of the Shadow Zone.

The samples returned assay values from trace up to 522.8 ppb Au, however, strongly anomalous (>50 ppb Au) samples were spotty and failed to define any significant trends. There were no significant multi-element anomalies noted in the samples either other than two samples that returned >100ppm Pb (up to 149.3 ppm).




Figure 18 – Gold in soils on the Shadow Zone showing 2016 sample locations.

Stewart Zone

A total of 197 soil samples were collected to the SE of the Stewart Zone. The samples were collected on a grid (100m spaced lines x 50m spaced samples) and were designed to follow up on a 'one-hit' gold in soil anomaly of 102 ppb Au within a saddle on a reconnaissance line. Assays for the samples failed to return any significant results with only two samples on the grid returning >10 ppb Au (10.7 and 13 ppb). Three samples returned >100 ppm As, however, they defined no discernible trends.




Figure 19 – Gold in soils on the Stewart zone showing 2016 sample locations.

5.4 RAB Drilling

A total of 2,423m of RAB drilling over 34 holes was conducted on the VG, Shadow, and Stewart Zones. The drilling was conducted by Ground Truth Exploration of Dawson City, YT using a heli-portable track mounted RAB drill capable of drilling up to 100m depth (locally 150m depth pending ground conditions).

The RAB Drill (Rotary Air Blast) is a remotely controlled tracked platform with an onboard air compressor, tilting mast and rotary drill head. The RAB Drill has 1650 sq. inches of track coverage with less than 1.0 psi ground pressure allowing it to be extremely versatile and low impact in the field. The entire unit is powered by a 60hp Turbo charged Kubota diesel engine and is completely air / hydraulically operated. Each drill hole is cased from surface to bedrock then an open hole hammer is used to penetrate into bedrock. Samples are collected every 5' (1.524 m) runs and assessed for volume (liters) to determine

sample recovery. The sample is then run through a 3 - tiered riffle splitter and approximately 1/8th of the sample is collected for analysis. Rock chip sample size is 1/4 – 3/8” and is analyzed and catalogued into chip trays. Additionally, a small portion of the sample is collected for analysis by XRF to guide interpretation and chip logging efforts.



Figure 20 – GT RAB Drill on the QV Property; drill hole 16QVVRAB-03.

Each drill site is surveyed using a DGPS for hole location and elevation. Additionally, each hole is surveyed using a QL40 OBI-2G Optical Borehole Imager (aka “Optical Televiewer”). The Optical Televiewer Instrument is a downhole imaging tool which provides a 360° image of the outer wall of any borehole filled with air or clear water. The tool also provides a high resolution downhole magnetic, inclinometer, gravity survey which provides an azimuth and dip survey throughout the borehole. The tool is operated via an electric winch which lowers the tool into a borehole, data is viewed in real time via laptop. The Data is recorded as a .tfd file which can later be used for structural interpretation and geological logging in WellCAD software.

VG Zone

A total of 1,752.8m over 24 holes were drilled on the VG Zone. The purpose of the drilling was to test the eastern and western extents of known mineralization on the VG Zone to define targets for follow up diamond drill testing. Hole depths ranged from 15.24m – 141.72m, averaging 73.02m. Several of the holes were terminated before target depth due to unstable ground conditions and/or significant groundwater.

Table 1 - 2017 VG Zone RAB Collars

Hole ID	Easting	Northing	Elevation	Azimuth	Dip	Depth
16QVV001	574627	7015937	517	340	-60	96.01
16QVV002	574627	7015937	517	160	-60	100.58
16QVV003	574656	7016017	539	160	-60	100.58
16QVV004	574665	7016127	517	340	-65	121.92
16QVV005	574731	7016158	560	160	-65	28.96
16QVV006	574703	7016220	573	160	-85	94.49
16QVV007	574783	7016227	590	160	-60	100.58
16QVV008	574813	7016165	582	160	-65	141.72
16QVV009	574895	7016225	586	160	-65	134.11
16QVV010	574713	7016197	586	160	-55	45.72
16QVV011	574705	7016095	544	160	-55	100.58
16QVV012	574710	7016103	545	340	-50	32
16QVV013	574506	7016286	498	160	-60	64.01
16QVV014	574519	7016196	483	160	-55	82.3
16QVV015	574520	7016192	482	20	-60	41.15
16QVV016	574546	7016058	469	160	-60	67.06
16QVV017	574358	7016049	531	160	-80	114.3
16QVV018	574358	7016049	521	340	-70	103.63
16QVV019	574301	7015934	508	160	-60	15.24
16QVV020	574296	7015934	505	160	-65	18.29
16QVV021	574299	7015940	508	160	-90	24.38
16QVV022	574311	7015829	474	160	-60	22.86
16QVV023	574321	7015803	453	160	-60	19.81
16QVV024	573696	7015686	516	160	-60	82.3




Figure 21 - 2016 VG Zone RAB Plan.

Holes 16QVRAB001-004 were drilled approximately 150-200 m south of the main VG zone to investigate combined soil-GT Probe and resistivity anomalies. Further work is required to determine the significance of, and controls to, the 3.05 m at 7.79 g/t gold intersected starting at 4.57 m down hole in 16QVRAB001. This intercept is located considerably south of the VG zone proper and may represent a parallel mineralized structure. Results for RAB holes 16QVRAB002-4 included numerous anomalous samples of up to 0.412 g/t gold over 1.52 m, all associated with broad (up to 50m) zones of strong quartz-sericite +/- clay alteration.

Holes 16QVRAB005-7 and 10 were drilled to the north of the interpreted location of the east-trending Telegraph fault in an area mapped as being underlain by amphibolite. Holes 16QVRAB005 and 10 were terminated well before reaching their target depths due to strong faulting and fracturing in the rock adjacent to the Telegraph fault. 16QVRAB006,

targeting a resistivity low at approximately 80 m depth, was collared in amphibolite and transitioned into felsic gneiss at approximately 54m depth; immediately above the mineralized intercept which starts at 59.44 m depth and continues to the end of the hole. 16QVRAB007, drilled 80 m to the east of 16QVRAB006, did not reach the resistivity low it was targeting but intersected anomalous gold up to 1.52 m at 0.402 g/t gold in the bottom quarter of the hole.

Holes 16QVRAB008, 9, 11 and 12 were all drilled south of the Telegraph fault. 16QVRAB011 and 12 collared in the eastern extension of the VG deposit, 55 m east of core hole QV13-013. Both holes cut strongly quartz-sericite-clay altered felsic gneiss with abundant oxidized pyrite. The distance between the base of the zone in the two holes is 25 m and sectional interpretation indicates the mineralized zone in this area dips to the north at 25-30°. Holes 16QVRAB008 and 9 were drilled to test a combined GT Probe-soil-resistivity target on the south side of the Telegraph fault, 165m and 265m, respectively, to the east of core hole QV13-013. Both holes collared in amphibolite and intersected 20m wide zones of chlorite-epidote+/-sericite alteration near surface, with anomalous gold values ranging from trace to 0.459 g/t over 1.52 m. Insufficient information is available to determine if these anomalous zones are related to an eastern extension of the VG zone, however, they do indicate the potential for mineralization within the amphibolite and further drilling in this area is required.

Holes 13 to 15 (16QVRAB013-015) were drilled on the northeastern flank of the VG deposit, in the north-south oriented draw and east of diamond drill holes QV12-03 and 07 and QV13-14 and 16, in order to test for extensions to the deposit in this area. Hole number 13 (16QVRAB013) reached a depth of 64.01 m before it was abandoned due to high water flow and low recovery prior to reaching its target depth of 100m, intersecting locally anomalous gold values.

Hole number 14 (16QVRAB014) was collared 40 m southeast of hole number 7 (QV12-007) and was drilled to the south at -55° intersecting a wide zone of gold mineralization, averaging 0.52 g/t gold over 64.01 m, starting at 16.76 m down hole and continuing until the end of the hole at 82.3 m depth. The upper part of the intercept included a 10.67 m interval averaging 1.65 g/t gold from 16.76 m down hole.

Hole number 15 (16QVRAB015), collared from the same site as hole number 14 (16QVRAB014), was drilled towards an azimuth of 20° in order to test for extensions further to the northeast. It intersected 4.57 m averaging 1.03 g/t gold at the bottom of the hole and was stopped at only 41.15m depth due to high water flow and low recovery. It is interpreted to have been just entering the zone of interest. Although the RAB holes did

not transect the full thickness of the mineralized zone in the area, they are important as they demonstrate that the VG zone mineralization continues to the NE of the current resource area. Furthermore, when combined with previously reported RAB hole number 6 (16QVV006), it indicates over 200m of strike potential to the NE direction that should be tested with follow-up diamond drilling.

Hole number 16 (16QVRAB016) was drilled just to the south of the VG deposit and intersected anomalous gold over the top 24.38 m of the hole.

Holes number 17 (16QVRAB017) and hole number 18 were drilled from a single pad 50 m north of diamond drill hole hole number 12 (QV13-012) on the western flank of the VG deposit. Hole number 17 (16QVVRAB-017), drilled to the south at -80° , intersected an upper zone of 12.19 m at 1.59 g/t gold from 24.38 m to 36.58 m down hole and a lower zone of 57.91 m averaging 1.89 g/t gold from 56.39 m to the end of the hole at 114.30 m, separated by 19.81 m with anomalous gold values. The lower intercept included a high-grade section of 12.19 m averaging 5.53 g/t gold from 83.82 m to 96.01 m down hole.

Hole number 18 (16QVRAB018), drilled to the north at -70° , intersected 4.57m at 0.99 g/t gold from 36.58 to 41.15 m and 18.29 m averaging 1.14 g/t gold between 85.34 m and 103.63m down hole, ending in the mineralized zone due to high water and loss of recovery. Together the hole 17 & 18 extended the VG deposit 100m down dip of QV13-12; it remains open and untested to the west in this area.




Figure 22 - Cross-section of drill holes QV13-12, 16QVV017, & 16QVV-18 with resistivity.

Holes number 19 to 21 (16QVRAB019-021) were drilled from a single pad located 90 m southwest of QV13-012. All three holes were abandoned far short of their target depths due to strongly fractured/broken ground associated with faulting in the area; hole number 19 (16QVRAB019), however, intersected 6.10 m averaging 0.21 g/t gold from 7.62 to 13.72 m depth.

Holes number 22 to 23 (6QVRAB022-23) were drilled 110 & 135m downhill, respectively, to the south of holes number 19 to 21 (16QVRAB019-021) in order to test the western extent of the VG zone soil anomaly and anomalous GT Probe samples in the area. These holes were also abandoned short of target depth due to strongly oxidized and highly fractured ground conditions; both intersected gold mineralization over most of their lengths.

Table 2 - Summary of Assays from 2017 RAB Drilling on the VG Zone.

Hole ID	From(m)	To(m)	Interval (m)	Au (g/t)
16QVV001	4.57	7.62	3.05	7.79
16QVV002	No Significant Intercepts			
16QVV003	No Significant Intercepts			
16QVV004	No Significant Intercepts			
16QVV005	No Significant Intercepts			
16QVV006	54.44	94.49	35.05	0.46
<i>Including</i>	54.44	79.25	19.81	0.56
16QVV007	No Significant Intercepts			
16QVV008	No Significant Intercepts			
16QVV009	No Significant Intercepts			
16QVV010	No Significant Intercepts			
16QVV011	0	19.81	19.81	1.22
<i>Including</i>	0	6.10	6.10	3.65
16QVV012	0	21.34	21.34	1.57
<i>Including</i>	0	13.72	13.72	2.33
16QVV013	38.10	39.62	1.52	1.41
16QVV014	16.76	56.39	39.62	0.74
<i>Including</i>	16.76	27.43	10.67	1.65
16QVV015	35.05	39.62	4.57	1.03
	*Hole ended in mineralization			
16QVV016	0	24.38	24.38	0.18
16QVV017	24.38	114.3	89.92	1.45
<i>Including</i>	56.39	106.68	50.29	2.15
<i>Including</i>	83.82	103.63	19.81	4.19
<i>Including</i>	83.82	96.01	12.19	5.53
	*Hole ended in mineralization			
16QVV018	36.58	41.15	4.57	0.99
<i>And</i>	85.34	103.63	18.29	1.14
	*Hole ended in mineralization			
16QVV019	7.62	13.72	6.10	0.21
16QVV020	No Significant Intercepts			
16QVV021	No Significant Intercepts			
16QVV022	1.52	12.19	10.62	0.25
<i>Including</i>	10.67	12.19	1.52	1.37
16QVV023	0	16.76	16.76	0.33
<i>Including</i>	1.52	7.62	6.10	0.60
16QVV024	35.05	44.20	9.15	0.329

Shadow Zone

A total of 399.29m over 7 holes were drilled on the Shadow Zone. The drilling tested approximately 460m of strike length along a linear, NW trending, gold in soil anomaly that is coincident with a significant resistivity low feature (Spirit Fault). With exception of hole 16QVV025, the drilling was hampered by poor ground conditions and groundwater.

Table 3 - 2017 Shadow Zone Drill Collars

Hole ID	Easting	Northing	Elevation	Azimuth	Dip	Depth
16QVV025	568757	7026647	528	0	-60	100.58
16QVV026	568954	7026507	467	0	-60	51.82
16QVV027	569069	7026493	456	0	-60	36.58
16QVV028	569170	7026444	439	0	-60	73.15
16QVV029	568997	7026591	506	180	-70	62.48
16QVV030	569045	7026568	485	180	-60	25.91
16QVV031	569045	7026568	483	180	-80	48.77




Figure 23 - 2016 Shadow Zone RAB Plan with gridded gold in soils and IP-Resistivity lines.

No significant results were returned from the drilling with assay values ranging from below detection to 1.065 g/t (over 1.524m). The best intercept was from hole 16QVV029 and averaged 0.662 g/t Au over 9.14m. The mineralization in the area is associated with elevated As, Bi, Mo, Te, and W and quartz-sericite alteration within a potassium feldspar rich (altered?) orthogneiss. A distinct quartz eye porphyry intrusive also occurs along the trace of the Spirit Fault, however, it is indistinguishable from the host orthogneiss in the RAB chips and is unclear if it is associated with mineralization in the area. Overall, the area displays strong similarities to mineralized occurrences on the Rosebutte property, approximately 10km to the north.

Table 4 - Summary of Assays from 2017 RAB Drilling on the Shadow Zone.

Hole ID	From(m)	To(m)	Interval (m)	Au (g/t)
16QVV025	38.10	53.34	15.24	0.225
16QVV026	No Significant Intercepts			
16QVV027	4.57	24.38	19.81	0.204
16QVV028	45.72	47.24	1.52	0.53
16QVV029	53.34	62.48	9.14	0.662
<i>Including</i>	59.44	60.96	1.52	1.07
16QVV030	No Significant Intercepts			
16QVV031	No Significant Intercepts			

Stewart Zone

A total of 271.8m over 3 holes were drilled on the Stewart Zone. All three holes were conducted from the same drill site with hole 16QVV033 failing due to casing issues. Additional holes were planned for the Stewart area, however, were abandoned for safety considerations (fall weather conditions and decreasing daylight).

Table 5 - 2017 Stewart Zone RAB Collars

Hole ID	Easting	Northing	Elevation	Azimuth	Dip	Depth
16QVV032	576252	7020498	628	0	-60	147.83
16QVV033	576255	7020499	629	90	-60	13.72
16QVV034	576253	7020502	632	0	-90	109.73

No significant results were returned from the drilling with assay values ranging from below detection to 0.318 g/t (over 1.524m). However, a broad zone of anomalous mineralization was encountered in hole 16QVV032 (64.01m of 0.103 g/t Au) and is coincident with elevated Bi, Cu, Mo, Se, Te, and W. The mineralization is hosted within a pervasively silicified felsic gneiss and, locally, amphibolite with stockwork quartz veining and >5% disseminated sulfides. Sericitically altered quartz feldspar porphyry

dikes are also common in the area, but were not intercepted during the drilling, and their relationship to mineralization is currently unknown.

Table 6 - Summary of Assays from 2017 RAB Drilling on the Stewart Zone.

Hole ID	From(m)	To(m)	Interval (m)	Au (g/t)
16QVV032	60.96	124.97	64.01	0.103
<i>Including</i>	108.20	124.97	16.76	0.185
16QVV033	No Significant Intercepts			
16QVV034	No Significant Intercepts			




Figure 24 - Stewart Zone 2016 RAB Plan with gridded gold in soils and GT Probe sampling.

5.5 Sample Preparation, Laboratory Analysis, and QA/QC

All samples collected on the QV Project in 2016 were sent to Bureau Veritas Laboratories (“BV”) for preparation and analysis. After field collection, all samples were returned in

labelled rice bags to Ground Truths yard in Dawson City, YT where the samples were inspected and sample numbers verified versus GT's database. The samples were then shipped to BV's preparation laboratory in Whitehorse, YT and prepared for analysis per requested protocols. Finally, a pulp of the sample was sent to BV's Vancouver laboratory for final preparation and analysis. Specific methodologies utilized are summarized below.

Soils

All soil samples were prepared using procedure SS80 (crush, split, and pulverize 250g of material to -200 mesh) and analyzed by methods FA430 (30g Fire Assay with AAS finish) and AQ200 (aqua-regia digest of 0.5g of material followed by ICP-MS analysis for 37 elements).

Rock, GT Probe, & RAB Samples

All rock (RAB and GT Probe) samples were prepared using procedure PRP70-250 (dry at 60° C and sieve 100g of material at -80 mesh) and analyzed by method AQ201 (aqua-regia digest of 15g of material followed by ICP-MS analysis for 37 elements).

QA/QC

The reported work was completed using industry standard procedures, including a quality assurance/quality control program ("QA/QC"). For soil samples, a field duplicate was inserted into the sample stream every 25th samples. For RAB samples alternating QA/QC samples consisting of a certified standard, coarse blank, or duplicate were inserted into the sample stream every 10th sample. No specific QA/QC samples were inserted in the field for prospecting or GT Probe samples, however, certified standard, blank, and duplicates were inserted in to the sample stream by the laboratory. The QA/QC data for the project has been reviewed by the author and no significant QA/QC issues were noted.

6 Interpretation and Recommendations

A multi-phase exploration program is recommended on the QV property. This includes diamond drilling on VG Zone, systematic (re)evaluation of the Stewart, Korat-Tetra, and Shadow target areas, and renewed property wide reconnaissance efforts. In all a total of 2,000m of diamond drilling has been proposed on the VG zone over an estimated 12 – 15 holes; an estimated 2,050 grid soil samples over the VG, Stewart, Korat-Tetra, and Shadow areas; and an estimated 950 reconnaissance soil on un/under explored portions of the property and on adjacent, open, ground to the NW of the property. DC IP-Resistivity surveys and/or GT Probe surveys should also be considered on certain target areas

pending initial results. An estimated budget for the proposed program is approximately \$1.25 million not including potential follow-up working with DC IP-Resistivity or GT Probe surveys.

6.1 VG Zone

Approximately 2,000m of diamond core drilling is recommended on the VG Zone. The holes are designed to test the potential for near surface extensions to the VG on strike to the east and west. Currently 10 holes have been laid out for discussion/consideration totaling 1,500m with projected hole depths range from 50 – 200m depth, averaging 150m. The holes were placed based on an interpreted and projected model of the 'top' surface (hanging wall) of the VG zone constructed in Leapfrog using the current diamond and RAB drill hole database. All holes are designed to intercept the projected within 100m depth (or less) and would trans-sect the full VG zone assuming an average 30m thickness.

Seven of the holes are designed to test the potential western extent of the VG with the first hole planned to either twin, or drill between, 2016 RAB holes 16QVV017 & 018. Successive fences of 2-3 holes would be placed on 2 – 100m step outs with 2-3 holes from each fence. If successful, the drilling would add an estimated 200m of strike extent to the west and trace mineralization up to 150m down dip along this area.

Three of the holes are designed to test the eastern extent of the VG Zone, north of the Telegraph Fault. The current interpretation for this area is that the VG zone continues to the east-northeast but is cut-off by the Telegraph fault just below surface (estimated 20 – 30m depth) and is a blind target. This is supported by 2016 RAB drilling (16QVV06, 13, & 14) where VG style alteration and mineralization was intercepted at the bottom of the holes before they were lost due to high groundwater output. Mineralization observed and intercepted on the south side of the Telegraph Fault is interpreted as representing footwall remnants of the faulted off-set of the VG Zone. This interpretation is based on the location of the mineralization relative to the Telegraph Fault and prevalence of footwall style alteration consisting of potassium feldspar and specular hematite below and adjacent to the mineralization in the area. There is an indication in the model that the Telegraph fault dips steeply to the south which would indicate a reverse sense of offset along it. However, I think this is a function of how Leapfrog has extrapolated the modeled plane and interpret the Telegraph Fault as being near vertical with a normal to sinistral sense of offset (down to the north); which is in line with current regional scale interpretations. If this interpretation is correct and the drilling is successful, this would extend the VG zone approximately 185m to the east-northeast.

An additional 500m of drilling has been included in the recommendations as contingency to follow-up on the planned holes above should there be exploration success.




Figure 25 - Plan map of the VG Zone with historic and proposed drilling and the modelled surface trace of the VG Zone (red dotted line), the VG footwall zone (orange dotted line), and the Telegraph Fault. The blue lines represent a series of sections from Leapfrog presented in following Figures 26 – 28.




Figure 26 - Cross-section along drill holes QV13-012, 16QVV017, & 16QVV018 showing interpreted surface of mineralization (red plane) and interpolated grade shells (red = > 1g/t Au, orange = >0.5 g/t Au).




Figure 27 - Oblique view of 200m wide long section of the VG Zone showing proposed western drill holes and estimated interception with the model VG zone surface (red).




Figure 28 - Oblique view of 200m wide cross section of the eastern VG Zone showing proposed eastern drill holes and estimated interception with the model VG zone surface (red).

An estimated 240 infill soils are also proposed for the VG Zone. The eastern infill grid is along the surface trace of the Telegraph Fault. This will complete a coherent infill grid to the east and is designed to test for any potential near surface mineralization along the Telegraph fault not highlighted in the current grid. The western block is designed to infill and completed the soil grid to the immediate west of the VG Zone. There are 1.) some missing samples in this area, 2.) evidence of alteration in drone imagery of the area, 3.) existing, but coarse, soil anomalies (Au - Mo), and 4.) some evidence from previous RAB and diamond drilling of potentially mineralized cross-faults or splays that could come to surface in this area.




Figure 29 - Proposed infill soil grids on the VG Zone.

6.2 Korat - Tetra Area

The Korat-Tetra area is comprised of an approximately 3.1km W-NW area bordered by the Tetra target on the East and Chris Creek to the west. It consists primarily of new claims staked in 2016 and previously saw limited exploration by Northern Tiger Resources including wide spaced soil sampling and an airborne geophysical survey. Of interest, is a W-NW trending magnetic low that is on trend with Tetra anomaly on the east and a 135.6 ppb gold in soil sample in a reconnaissance line to the west. Northern Tiger placed 3 wide spaced (~700m spaced lines and 100m spaced samples) soil lines across the area that returned weakly anomalous Au (up to 15 ppb Au) and anomalous Mo (up to 20 ppm Mo) coincident with the magnetic low. Although the gold values are low, it should be noted that they are B-Horizon soils which is not as effective of a sampling method in the region; particularly for gold. Therefore, any gold response in the B-horizon soils is considered significant and, combined with the associated of elevated Mo and the

magnetic low, the area is considered a priority target. Grid soil sampling (100m spaced lines x 50m spaced samples ~1,000 samples) targeting C-horizon material is recommended across area. Reconnaissance, ridge and spur, could also be conducted but given the size of the target area you risk potentially missing anomalous areas. Additionally, the associated geochemistry from the grid soils would be very useful for geologic mapping and interpretation efforts.




Figure 30 - Proposed infill soil grid in the Korat-Tetra area with TMI airborne magnetics and gold in soils from Northern Tiger.

6.3 Stewart Area

Additional work should be considered on the Stewart target. While the results of 2016 RAB drilling were not spectacular, the drilling only tested a small portion of the target and the size and tenure of the alteration encountered indicate there was significant

hydrothermal activity in the area. Based on interpretation from geophysical (mag & IP-Res), geochemical, and the RAB data the Stewart appears to be associated with an E-W trending structure. However, that interpretation is tenuous based on the available data and the observed alteration/mineralization could also be related to thermal alteration from felsic intrusive rocks immediately north of the target area rather than a pure structural control. While additional drilling is recommended on the Stewart it should follow additional efforts to refine the target and interpretation. Specific recommendations are an aerial drone survey of the area to refine the topography, infill soil sampling on 50m spaced line x 25m spaced samples (~650 samples) to better define the soil anomaly, and additional geologic mapping.




Figure 31 - Proposed infill soil grid on the Stewart Zone with Mo in soils over gridded Au in soils.

6.4 Shadow Area

Recommended work in the Shadow area should focus on follow up work on a +400m, NW trending, Au – Bi – Mo – Pb soil anomaly along a NE facing slope adjacent to the Yukon River. No prior follow-up work has been conducted on the anomaly other than infill soil sampling; to the authors knowledge. The current soil grid to should be expanded on trend of the anomaly to the NW and SE and geologic mapping/prospecting should be conducted in the area. An initial IP-Resistivity survey should also be considered and, potentially, GT Probe sampling pending topographic conditions. There are some indications that the soil anomaly lies along a NW oriented structure based on Google Earth imagery of the area, but the imagery is coarse, and a drone survey of the broader Shadow area is recommended to provide better topography and imagery to aid in geologic mapping/interpretation efforts.




Figure 32 - Proposed grid soils in the Shadow area with Mo in soils over gridded gold in soils.

6.5 Estimated Budget

An estimated budget for the proposed work is summarized below:

Diamond Drilling

Est. 2,000m @ \$500/m (all-in) = \$1,000,000

Soil Sampling

Est. 3,000 samples @ \$65/sample (all-in) = \$195,000

Drone Surveys

Est. \$30,000

Geologic mapping, prospecting, interpretation, and reporting

Est. \$25,000

Total = Est. \$1.25 million

7 Costs

GEOLOGIC MAPPING/PROJECT MANAGEMENT		
Geologist/Project Management	Amount	Description
Wages	\$ 1,760.00	Project management
Field Equipment/Electronics	\$ 270.00	
Sampling Supplies	\$ -	
Program Prep, Mobe/Demobe Rate, Expediting	\$ -	
Reporting/Data Interpretation/Data Mangement	\$ 800.00	
Total Geologist/Project Management	\$ 2,830.00	
GEOCHEMICAL SURVEYS		
Soil/Till Survey	Amount	Description
Wages	\$ 7,370.00	4 days x 5 man crew
Soil Survey Equipment	\$ 1,320.00	
Program Prep, Mobe/Demobe Rate, Expediting	\$ 3,452.50	
Additional Supplies and Support	\$ 2,180.00	Remote camp set-up, food, etc.
Sampling Supplies	\$ 1,127.50	451 total samples
Transportation Support	\$ -	
Total Soil/Till Surveys	\$ 15,450.00	
GT Probe Survey	Amount	Description
Wages	\$ 32,175.00	19.5 days x 3 man crew
GT Probe Equipment & Field Electronics	\$ 19,050.00	
Program Prep, Mobe/Demobe Rate, Expediting	\$ 4,462.50	
Additional Supplies and Support	\$ 12,800.00	Remote camp set-up, food, etc.
Sampling Supplies	\$ 1,436.00	360 total samples
Transportation Support	\$ 710.00	
Total GT Probe	\$ 70,633.50	
GEOPHYSIAL SURVEYS		
DC IP-Resistivity Survey	Amount	Description
Wages	\$ 17,160.00	8 days x 5 man crew
IP-Res Survey Equipment	\$ 7,220.00	
Consumable Supplies	\$ 390.00	Stainless steel electrodes, calcium chloride, etc.
Program Prep, Mobe/Demobe Rate, Expediting	\$ 5,726.25	
Additional Supplies and Support	\$ 4,875.00	Remote camp set-up
Transportation Support	\$ -	
Total DC IP-Resitivity Surveys	\$ 35,371.25	
QUARTZ CLAIM STAKING		
Cost per claim (all-in)	\$ 3,410.00	
Total Quartz Claim Staking	\$ 3,410.00	
LABORATORY ANALYSIS		
Soil/Till Samples	Amount	Description
Prep	\$ 1,425.16	
Sample Disposal	\$ 202.95	
Sample Analysis	\$ 4,947.47	
Total Soil Sample Analysis	\$ 6,575.58	
Rock/Core Samples	Amount	Description
Prep	\$ 1,766.28	
Sample Disposal	\$ 161.55	
Sample Analysis	\$ 6,171.21	
Total Rock Sample Analysis	\$ 8,099.04	
LOGISTICAL SUPPORT		
Helicopter	Amount	Description
ASTAR B2 and/or Jet Ranger (3hr minimum)	\$ 54,069.94	29.2 Hours @ \$1767.5/hr - ASTAR B2 (wet) 2.1 Hours @ \$1170.40/hr - Bell 206 (wet)
Fixed Wing	Amount	Description
Islander, 206, Skyvan, etc.	\$ 2,609.57	Great River Air - 206 & Islander
Total Logistical Support	\$ 56,679.51	
Total Project Expenditures	\$ 199,048.88	

QV Project - 2016 RAB Drilling		
Comstock Metals 310 - 850 West Hastings St, Vancouver, BC V6C 1E1 David Terry - 604-639-4533 August 27 - Oct. 9, 2016		
GEOLOGIC MAPPING/PROJECT MANAGEMENT		
Geologist/Project Management	Amount	Description
Wages	\$ 3,080.00	Sr. Geo in field (3.5 days)
Field Equipment/Electronics	\$ 210.00	
Sampling Supplies	\$ -	
Program Prep, Mobe/Demobe Rate, Expediting	\$ -	
Reporting/Data Interpretation/Data Mangement	\$ 8,700.00	Sr. Geo database management, GIS, & QA/QC
Total Geologist/Project Management	\$ 11,990.00	
DRILLING		
GT RAB Drill	Amount	Description
Wages	\$ 112,200.00	RAB Driller, Assistant, & Sampler
GT RAB Drill Equipment & Field Electronics	\$ 123,840.00	RAB Drill, Compressor, and additional drilling equipment
Program Prep, Mobe/Demobe Rate, Expediting	\$ 2,477.50	
Additional Supplies and Support	\$ 68,610.00	Camp, food/expediting, OFA First Aid attendant & Cook, etc.
Sampling Supplies	\$ 4,869.00	2242 Samples
Fuel	\$ 14,770.80	
Transportation Support	\$ 1,128.00	
GT RAB Consumables	\$ 22,420.38	
Downhole Televiewer	\$ 44,723.80	Optical Televiewing equipment, operator, and interpretation
Total RAB Drilling	\$ 350,315.68	
LABORATORY ANALYSIS		
Rock/Core Samples	Amount	Description
Prep	\$ 17,218.56	
Sample Disposal	\$ 1,008.90	
Sample Analysis	\$ 38,539.98	2242 samples - 30g Fire Assay + multi-element ICP analysis
Total Rock Sample Analysis	\$ 56,767.44	
LOGISTICAL SUPPORT		
Helicopter	Amount	Description
ASTAR B2 and/or Jet Ranger (3hr minimum)	\$ 150,785.81	60.4 Total Hours
Fixed Wing	Amount	Description
Islander, 206, Skyvan, etc.	\$ 6,557.92	4 flights
Total Logistical Support	\$ 157,343.73	
OTHER/MISC		
Sampling Shipping	\$ 1,931.12	
Total Other/Misc	\$ 1,931.12	
Total Project Expenditures		\$ 729,133.78

8 References

Allan, M.M., Mortensen, J.K., Hart, C.J., and Bailey, L.A., 2012, Timing, nature, and distribution of Jurassic orogenic gold systems in the west-central Yukon. In: MDRU's Yukon Gold Project – Final Technical Report, May 2012. Allan, M.M., Hart, C.J., & Mortensen, J.K. (eds), pp.55 – 78.

Allan, M.M., Mortensen, J.K., Hart, C.J., and Sanchez, M., 2012, Current understanding of the metallogeny of the western Yukon and eastern Alaska. In: MDRU's Yukon Gold Project – Final Technical Report, May 2012. Allan, M.M., Hart, C.J., & Mortensen, J.K. (eds), pp.11 - 28.

Bailey, L.A., Allan, M.M., Hart, C.J., and Mortensen, J.K., 2012, Geology and mineralization of the Golden Saddle gold deposit, Yukon Territory. In: MDRU's Yukon Gold Project – Final Technical Report, May 2012. Allan, M.M., Hart, C.J., & Mortensen, J.K. (eds), pp.79 – 100.

Cooley, M. and Leatherman, L., 2013b, Results of geologic mapping, alteration mapping of drill core, and prospecting of the VG zone and recommendations for further exploration work at the QV property, Yukon. Report for Comstock Metals Ltd.

Deklerk, R. and Traynor, S. (compilers), 2005. Yukon MINFILE 2005 - A database of mineral occurrences. Yukon Geological Survey

Gordey, S.P. and Makepeace, A.J. (comp.) 2003. Yukon digital geology, version 2.0; Geological Survey of Canada Open File 1749 and Yukon Geological Survey Open File 2003-9(D)

Leatherman, L. and Cooley, M., 2013, Geology of the VG zone, QV property, Yukon. Report for Comstock Metals Ltd.

Paulter, J. and Shahkar, A., 2014, NI 43-101 Technical Report on the QV Project, White Gold district, Yukon Territory. 97p.

Ryan, J.J. and Gordey, S.P., 2004, Geology, Stewart River area, Yukon Territory. Geological Survey of Canada, Open File 4641.

Schulze, C.M., 2010, Assessment Report on the 2009 Geological and Geochemical Programs, Korat Property, Dawson Range, Yukon. Yukon Assessment Report #095279.

9 Statements of Qualification

I, Jodie L. Gibson, hereby certify that:

1. I am the Director of Exploration with Ground Truth Exploration., 109 Raspberry Lane, Dawson City, YT Y0B 1G0.
2. I am a graduate of Indiana State University, with a B. Sc. degree (2003) and a M.Sc. degree (2006) in Geology. I have been involved in geological mapping, mineral exploration and the management of mineral exploration companies continuously since 2007.
3. I am a member in good standing of the Association of Professional Engineers and Geoscientists of the Province of British Columbia, Registration No. 162701
5. The report is based on a literature review, private company reports, and on observations from the 2016 work program.
6. I designed, implemented, and managed the 2016 program on the QV Property.

Dated at Vancouver, B.C. this 2nd day of February, 2017.

<signed & sealed>

Jodie L. Gibson, P.Geo.

I, Adam Fage have continuously been involved in Mineral Exploration since 2004. I graduated from Dalhousie University with an Honours Bachelor of Science (Earth Science) in 2008. I graduated from Lakehead University with a Master's of Science (Geology) in 2011. I am a member, in good standing, of the Association of Professional Geoscientists of Ontario, Registration number 2256.

Dated this 2nd day of February, 2017.

Respectfully submitted

Adam Fage

**Geochemical, Geophysical, and RAB Drilling Survey
Assessment Report:
GT Probe, Soil Sampling, IP Survey, & RAB Drilling**

QV PROJECT

Volume II - Appendices

Claims:

QV 1-10	YC61008-017
QV 11-24	YC88221-8234
QV 25-72	YD13837-884
QV 73-188	YD13885-14000
QV 189-288	YD48801-48900
QV 289-342	YD47943-996
QV 343-494	YE21103-254
QV 495-524	YE76847-876
QV 525-714	YF03605 -794
QV 715-791	YF76235 -311
QV 792-822	YF00412-442

Dawson Mining District

NTS: 1150/05

Latitude: 63.16.2° N Longitude: -139.32.8 ° W

Soil Sampling Performed On: July 21-22 & 28-29, 2016

IP Survey Performed On: July 13 – 18 & 21 – 25, 2016

GT Probe Performed On: July 9 – 29, 2016

RAB Drilling Performed On: August 27 – November 9, 2016

Prepared for Comstock Metals Ltd.

By GroundTruth Exploration

Written by: Jodie Gibson, P.Geo. & Adam Fage, P.Geo.

August 19, 2017


Appendix A: IP Resistivity Profiles

QV Property – VG Zone

2016 DC IP-Resistivity Section QVIP16-33


All sections are looking SW

Inverted IP Section



Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 16, 2016
Traverse	QVIP16-33	Instrument	SuperSting R8
Array	Di-DI + Schlumb Inv.	Software	EarthImager 2D
Data File	160716D1S1-merge_trial1.stg		

Inverted Resistivity Section




Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 16, 2016
Traverse	QVIP16-33	Instrument	SuperSting R8
Array	Di-DI + Schlumb Inv.	Software	EarthImager 2D
Data File	160716D1S1-merge_trial1.stg		

QV Property – VG Zone

2016 DC IP-Resistivity Section QVIP16-34


All sections are looking SW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 16, 2016
Traverse	QVIP16-34	Instrument	SuperSting RS
Array	D-D + Schl Inv	Software	Earthmager 2D
Data File	1607160282_res2.sig		

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 16, 2016
Traverse	QVIP16-34	Instrument	SuperSting RS
Array	D-D + Schl Inv	Software	Earthmager 2D
Data File	1607160282_res2.sig		

QV Property – VG Zone

2016 DC IP-Resistivity Section QVIP16-35


All sections are looking SW

Inverted IP Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 17, 2016
Traverse	QVIP16-35	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv	Software	EarthImager 2D
Data File	160717D1S1_trial.slg		

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 17, 2016
Traverse	QVIP16-35	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv	Software	EarthImager 2D
Data File	160717D1S1_trial.slg		

QV Property – VG Zone
2016 DC IP-Resistivity Section QVIP16-36
All sections are looking SW



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 18, 2016
Traverse	QVIP16-36	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv	Software	EarthImager 2D
Data File	160718D1S1_trials.sgy		




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 18, 2016
Traverse	QVIP16-36	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv	Software	EarthImager 2D
Data File	160718D1S1_trials.sgy		

QV Property – VG Zone

2016 DC IP-Resistivity Section QVIP16-37


All sections are looking SW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 18, 2016
Traverse	QVIP16-37	Instrument	SuperSling R8
Array	Dx-Dx + Schl Inv	Software	Earthlogger 2D
Data File	160718D282_trial5.sig		


Inverted Resistivity Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 18, 2016
Traverse	QVIP16-37	Instrument	SuperSling R8
Array	Dx-Dx + Schl Inv	Software	Earthlogger 2D
Data File	160718D282_trial5.sig		


QV Property – VG Zone
2016 DC IP-Resistivity Section QVIP16-38
All sections are looking SW

Inverted IP Section



Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 19, 2016
Traverse	QVIP16-38	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160719D1S1	trial5	stg

Inverted Resistivity Section




Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 19, 2016
Traverse	QVIP16-38	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160719D1S1	trial5	stg

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-39


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 24, 2016
Traverse	QVIP16-39	Instrument	SuperSting RS
Array	D-D + Schl Inv	Software	EarthImager 2D
Data File	160724D1S1	trial9.sig	

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 24, 2016
Traverse	QVIP16-39	Instrument	SuperSting RS
Array	D-D + Schl Inv	Software	EarthImager 2D
Data File	160724D1S1	trial5.sig	

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-40


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 24, 2016
Traverse	QVIP16-40	Instrument	SuperSting R8
Array	DI-DI + Schl. Inv.	Software	Earthmager 2D
Data File	1607240282_trial15.stg		

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 24, 2016
Traverse	QVIP16-40	Instrument	SuperSting R8
Array	DI-DI + Schl. Inv.	Software	Earthmager 2D
Data File	1607240282_trial10.stg		

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-41


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 25, 2016
Traverse	QVIP16-41	Instrument	SuperSting R8
Array	DI-DI + Schl. Inv.	Software	EarthImager 2D
Data File	160725D1S1_trial10.stg		


Inverted Resistivity Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 25, 2016
Traverse	QVIP16-41	Instrument	SuperSting R8
Array	DI-DI + Schl. Inv.	Software	EarthImager 2D
Data File	160725D1S1_trial6.stg		


QV Property – Shadow Zone
2016 DC IP-Resistivity Section QVIP16-42
All sections are looking NW

Inverted IP Section



Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 26, 2016
Traverse	QVIP16-42	Instrument	SuperSting R8
Array	D-Di + Schl. Inv.	Software	Earthmager 2D
Data File	160726D1S1_trial10.stg		

Inverted Resistivity Section




Ground Truth Exploration Inc.			
Property	QV	Survey Date	Jul 26, 2016
Traverse	QVIP16-42	Instrument	SuperSting R8
Array	D-Di + Schl. Inv.	Software	Earthmager 2D
Data File	160726D1S1_trial3.stg		

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-43


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 27, 2016
Traverse	QVIP16-43	Instrument	SuperSting R8
Array	Di-Dx + Schl Inv	Software	EarthImager 2D
Data File	160727D1S1	read1.mg	

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 27, 2016
Traverse	QVIP16-43	Instrument	SuperSting R8
Array	Di-Dx + Schl Inv	Software	EarthImager 2D
Data File	160727D1S1	read1.mg	

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-44


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 27, 2016
Traverse	QVIP16-44	Instrument	SuperSling R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160727D2S2_tral8.stg		

Inverted Resistivity Section




GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 27, 2016
Traverse	QVIP16-44	Instrument	SuperSling R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160727D2S2_tral3.stg		

QV Property – Shadow Zone

2016 DC IP-Resistivity Section QVIP16-45


All sections are looking NW

Inverted IP Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 26, 2016
Traverse	QVIP16-45	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160726D2S2_trial8.stg		

Inverted Resistivity Section



GroundTruth Exploration Inc.			
Property	QV	Survey Date	Jul 26, 2016
Traverse	QVIP16-45	Instrument	SuperSting R8
Array	Di-Di + Schl. Inv.	Software	EarthImager 2D
Data File	160726D2S2_trial5.stg		

Appendix B: Soil Samples Assay Certificate



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 02, 2016
Report Date: August 09, 2016
Page: 1 of 9

CERTIFICATE OF ANALYSIS

WHI16000144.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV-2016-07-29-Soil
P.O. Number
Number of Samples: 238

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT-SOIL Immediate Disposal of Soil Reject

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1
CANADA

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Dry at 60C	238	Dry at 60C			WHI
SS80	238	Dry at 60C sieve 100g to -80 mesh			WHI
AQ201	238	1:1:1 Aqua Regia digestion ICP-MS analysis	15	Completed	VAN
SHP01	238	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 2 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	AQ201																				
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1390385	Soil	0.8	29.0	10.9	89	0.1	27.6	11.5	490	2.68	9.3	1.1	3.7	4.1	47	0.4	0.6	0.2	56	0.76	0.082
1390384	Soil	1.3	32.6	17.0	74	0.1	30.6	12.2	539	2.77	10.2	0.7	2.8	3.3	57	0.2	0.8	0.2	59	1.46	0.078
1390399	Soil	1.7	40.1	24.2	79	<0.1	34.0	11.4	476	3.21	20.0	1.1	3.4	7.0	27	<0.1	0.6	0.3	50	0.43	0.065
1390391	Soil	2.7	64.5	37.1	193	<0.1	61.2	18.9	1005	4.99	10.1	2.0	3.2	17.7	21	0.3	0.4	0.3	87	0.35	0.096
1390390	Soil	2.6	44.4	40.5	148	<0.1	33.1	12.1	484	3.98	15.7	1.5	0.7	9.0	20	0.3	0.6	0.3	66	0.17	0.069
1390398	Soil	2.4	49.2	24.9	108	<0.1	54.0	20.4	629	4.76	7.0	1.4	1.7	14.9	29	<0.1	0.3	0.1	71	0.48	0.076
1390389	Soil	4.7	38.1	24.7	79	0.2	29.7	9.0	512	2.73	6.9	0.6	3.5	0.6	11	<0.1	0.4	0.2	66	0.09	0.063
1390397	Soil	1.1	74.4	16.4	123	0.1	106.5	33.1	1033	5.72	6.8	0.9	1.5	8.4	113	0.1	0.4	0.1	126	3.66	0.138
1390388	Soil	0.4	19.1	11.2	74	<0.1	19.5	5.7	194	2.01	5.4	0.9	2.5	4.4	32	0.2	0.5	0.2	44	0.48	0.071
1390396	Soil	0.6	69.6	5.7	76	<0.1	151.4	38.0	674	5.01	1.5	0.5	<0.5	6.0	154	<0.1	0.1	<0.1	121	2.90	0.238
1390394	Soil	2.4	36.6	44.1	95	0.2	34.4	14.7	919	4.40	6.6	1.4	2.0	16.6	28	<0.1	0.4	1.1	41	0.54	0.052
1390395	Soil	2.7	29.9	21.7	66	<0.1	36.2	12.7	451	2.67	5.3	2.4	0.9	3.5	81	0.2	0.4	0.2	47	1.82	0.066
1390393	Soil	2.0	30.3	18.3	70	<0.1	34.6	12.8	578	3.46	8.4	0.8	3.2	10.8	26	<0.1	0.5	0.1	52	0.40	0.017
1390386	Soil	2.3	33.6	27.1	94	0.2	29.1	11.0	444	3.14	15.5	1.1	1.3	4.9	26	0.3	0.4	0.3	65	0.39	0.095
1390387	Soil	3.4	33.8	55.3	90	0.5	30.6	45.1	2908	3.70	11.7	1.5	4.3	3.8	17	0.3	0.3	0.3	76	0.22	0.091
1390400	Soil	2.0	58.2	29.0	90	0.2	36.5	16.7	862	4.34	22.1	1.1	4.3	5.9	27	0.1	0.6	0.3	56	0.48	0.075
1418608	Soil	0.6	36.4	15.3	84	0.1	40.5	16.2	663	3.86	14.2	1.6	1.3	6.1	49	0.2	0.4	0.2	63	1.11	0.067
1418606	Soil	1.1	47.6	15.9	96	<0.1	53.9	20.2	1186	3.89	8.4	1.7	13.0	16.5	24	<0.1	0.3	2.0	45	0.69	0.110
1390392	Soil	2.2	21.4	17.3	68	0.1	30.8	13.0	628	3.36	9.1	0.9	3.1	5.7	25	0.2	0.5	0.1	58	0.41	0.029
1418607	Soil	0.8	34.5	22.3	96	<0.1	39.7	15.3	416	3.92	13.7	1.2	0.8	12.4	21	<0.1	0.4	0.3	60	0.48	0.067
1418605	Soil	2.2	37.8	38.9	148	0.2	18.6	18.3	1167	5.86	26.4	1.3	6.0	10.6	20	0.1	0.8	0.3	82	0.55	0.083
1418604	Soil	1.1	39.8	16.2	120	<0.1	40.4	18.4	688	4.50	32.6	1.3	1.9	12.4	27	0.1	0.3	0.2	46	1.29	0.067
1418612	Soil	1.3	37.0	37.2	91	0.3	20.2	14.6	793	3.99	27.7	2.1	2.2	6.9	40	0.2	0.9	0.3	72	0.60	0.068
1418603	Soil	1.7	50.2	30.7	128	<0.1	42.4	13.0	400	4.06	41.5	2.3	4.0	10.3	26	0.1	1.3	0.4	48	0.33	0.060
1418611	Soil	1.1	36.7	31.6	85	0.2	29.4	18.2	666	4.70	32.9	1.6	4.4	9.1	27	0.1	0.6	0.4	74	0.47	0.057
1418602	Soil	2.1	50.4	42.3	131	<0.1	43.0	15.9	829	4.64	27.9	1.7	2.5	9.5	17	0.1	0.5	0.3	36	0.38	0.112
1418601	Soil	2.6	48.6	22.1	120	<0.1	39.0	14.2	473	4.62	31.7	1.9	1.2	11.1	18	<0.1	0.6	0.2	91	0.33	0.047
1418610	Soil	0.6	38.8	21.7	73	<0.1	38.8	17.9	486	4.04	17.0	1.7	3.9	13.7	16	<0.1	0.3	0.3	49	0.21	0.032
1418609	Soil	1.1	50.3	15.3	77	<0.1	39.2	19.9	637	4.00	27.6	1.6	<0.5	17.2	30	<0.1	0.6	0.3	47	0.58	0.055
1352829	Soil	1.2	16.4	11.2	50	0.2	23.9	9.1	215	2.88	13.3	0.6	2.9	3.9	19	<0.1	0.5	0.2	61	0.28	0.032



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 2 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte Unit MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te	
	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1390385	Soil	15	30	0.60	407	0.076	2	1.22	0.026	0.09	0.2	0.05	4.9	0.1	<0.05	4	<0.5	<0.2
1390384	Soil	15	33	0.79	302	0.082	2	1.35	0.034	0.08	0.1	0.03	5.1	<0.1	<0.05	4	<0.5	<0.2
1390399	Soil	18	29	0.37	370	0.029	<1	1.20	0.015	0.17	0.1	0.06	7.0	0.1	<0.05	4	0.7	<0.2
1390391	Soil	30	72	0.77	461	0.096	1	1.78	0.009	0.67	0.1	0.08	12.4	0.5	<0.05	7	0.9	<0.2
1390390	Soil	17	33	0.25	265	0.029	<1	1.31	0.007	0.13	<0.1	0.06	6.3	0.1	<0.05	4	<0.5	<0.2
1390398	Soil	46	69	0.99	397	0.139	2	2.18	0.016	0.78	0.1	0.03	8.3	0.4	<0.05	9	<0.5	<0.2
1390389	Soil	12	32	0.12	284	0.021	<1	0.83	0.008	0.10	0.1	0.02	2.7	0.1	<0.05	4	<0.5	<0.2
1390397	Soil	34	149	1.99	424	0.117	2	2.11	0.016	0.73	<0.1	0.07	13.5	0.5	<0.05	9	0.6	<0.2
1390388	Soil	14	26	0.47	349	0.067	1	1.10	0.018	0.08	0.2	0.06	4.2	<0.1	<0.05	4	<0.5	<0.2
1390396	Soil	33	227	3.19	618	0.173	<1	2.86	0.034	0.84	<0.1	0.03	7.7	0.4	<0.05	11	<0.5	<0.2
1390394	Soil	50	33	0.15	309	0.003	2	0.89	0.005	0.22	<0.1	0.15	12.0	0.2	<0.05	3	0.5	<0.2
1390395	Soil	16	54	0.32	382	0.025	3	0.78	0.014	0.18	<0.1	0.10	6.8	0.1	<0.05	3	0.9	<0.2
1390393	Soil	26	39	0.36	309	0.054	2	1.31	0.014	0.20	<0.1	0.05	8.2	0.1	<0.05	4	<0.5	<0.2
1390386	Soil	17	35	0.42	470	0.043	2	1.18	0.014	0.12	0.2	0.08	5.8	0.1	<0.05	4	<0.5	<0.2
1390387	Soil	20	43	0.32	701	0.032	1	1.38	0.009	0.20	0.1	0.11	7.1	0.2	<0.05	6	0.8	<0.2
1390400	Soil	21	29	0.45	405	0.014	3	1.42	0.015	0.23	<0.1	0.13	10.0	0.2	<0.05	4	0.5	<0.2
1418608	Soil	27	68	0.91	366	0.064	3	1.98	0.015	0.21	<0.1	0.12	12.2	0.2	<0.05	7	1.2	<0.2
1418606	Soil	49	49	1.32	264	0.047	2	2.28	0.009	0.43	0.3	0.10	8.4	0.4	<0.05	9	0.6	<0.2
1390392	Soil	14	41	0.36	547	0.051	3	1.44	0.011	0.17	0.1	0.05	7.0	<0.1	<0.05	4	0.6	<0.2
1418607	Soil	37	54	0.75	291	0.086	2	2.12	0.010	0.58	0.1	0.06	7.6	0.3	<0.05	9	<0.5	<0.2
1418605	Soil	35	33	1.25	333	0.106	1	2.47	0.009	0.68	<0.1	0.08	14.8	0.5	<0.05	11	0.7	<0.2
1418604	Soil	27	33	0.61	293	0.043	2	1.54	0.008	0.35	<0.1	0.06	9.3	0.2	<0.05	6	<0.5	<0.2
1418612	Soil	24	30	0.73	284	0.072	2	1.74	0.016	0.28	0.1	0.09	9.3	0.4	<0.05	7	1.1	<0.2
1418603	Soil	18	26	0.24	314	0.009	2	1.12	0.009	0.17	<0.1	0.05	8.5	0.2	<0.05	3	<0.5	<0.2
1418611	Soil	38	39	0.99	402	0.079	2	2.38	0.010	0.44	0.1	0.07	12.0	0.3	<0.05	10	1.1	<0.2
1418602	Soil	15	16	0.15	304	0.002	1	0.84	0.006	0.18	<0.1	0.03	8.9	0.1	<0.05	2	0.7	<0.2
1418601	Soil	26	46	0.89	426	0.142	2	2.39	0.011	0.73	<0.1	0.04	10.6	0.4	<0.05	10	0.7	<0.2
1418610	Soil	39	39	0.71	320	0.075	<1	1.98	0.011	0.17	0.1	0.01	6.5	0.2	<0.05	7	<0.5	<0.2
1418609	Soil	35	44	0.88	277	0.077	2	1.98	0.008	0.35	<0.1	0.05	8.6	0.2	<0.05	8	<0.5	<0.2
1352829	Soil	11	39	0.47	308	0.050	1	2.03	0.009	0.06	0.2	0.03	3.4	0.1	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 3 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	AQ201																				
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1352834	Soil	0.6	32.6	20.2	84	<0.1	28.9	13.4	339	3.98	7.0	2.1	0.9	19.8	20	<0.1	0.4	0.2	35	0.33	0.061
1352831	Soil	0.6	20.0	14.9	41	<0.1	16.8	7.5	167	2.07	14.8	0.9	1.6	3.8	22	<0.1	0.8	0.1	45	0.34	0.034
1352836	Soil	0.7	24.4	7.2	55	<0.1	34.5	16.0	387	3.09	6.4	0.6	2.2	2.7	19	<0.1	0.3	0.1	68	0.40	0.053
1352833	Soil	0.8	15.8	12.8	46	<0.1	16.7	8.2	228	2.37	11.6	0.5	<0.5	3.6	20	<0.1	0.7	0.2	50	0.24	0.034
1352832	Soil	0.6	16.9	13.7	36	<0.1	15.4	6.9	190	2.11	10.0	0.5	4.0	3.1	20	<0.1	0.6	0.2	48	0.25	0.020
1352837	Soil	1.0	14.1	11.7	65	<0.1	19.3	10.0	436	2.51	14.1	0.6	<0.5	2.8	24	0.2	0.4	0.2	54	0.44	0.041
1352828	Soil	1.4	60.9	7.0	96	<0.1	35.1	10.9	467	4.05	17.9	1.1	<0.5	8.4	11	<0.1	0.7	<0.1	51	0.10	0.024
1352827	Soil	1.2	18.0	9.0	56	<0.1	19.1	7.2	190	2.96	12.2	0.9	<0.5	5.4	14	<0.1	0.4	0.1	50	0.12	0.038
1352826	Soil	0.7	26.1	12.4	47	0.1	23.3	8.6	173	2.44	12.2	0.7	1.2	4.1	21	<0.1	0.6	0.1	52	0.23	0.028
1352830	Soil	0.1	34.6	6.2	59	<0.1	17.1	19.0	884	4.28	3.0	0.2	<0.5	1.3	20	<0.1	0.3	<0.1	72	3.88	0.051
1352835	Soil	1.1	16.2	8.5	80	<0.1	20.2	12.6	473	4.27	6.4	0.7	<0.5	5.6	21	<0.1	0.3	<0.1	72	0.34	0.048
1429344	Soil	1.1	17.9	11.1	48	<0.1	23.6	9.6	213	2.72	10.7	0.6	2.6	4.7	17	<0.1	0.6	0.1	56	0.22	0.025
1429338	Soil	1.4	288.8	20.5	112	<0.1	59.2	19.5	907	5.37	11.3	0.9	2.9	5.3	42	0.2	1.3	<0.1	150	1.91	0.123
1429337	Soil	6.3	40.0	36.4	149	0.2	45.7	17.7	927	4.75	198.5	1.0	1.6	2.8	55	1.5	3.8	0.3	144	4.15	0.183
1429336	Soil	1.1	25.2	9.0	49	0.1	21.9	12.0	582	2.56	8.9	1.7	2.1	2.5	52	0.1	0.6	0.1	49	1.03	0.080
1429343	Soil	1.7	35.1	18.5	43	<0.1	25.3	10.0	199	2.78	62.1	1.6	1.4	9.7	21	<0.1	4.3	0.3	32	0.15	0.015
1429340	Soil	1.0	40.9	15.4	76	<0.1	34.3	14.8	499	4.36	5.6	1.7	1.7	16.6	20	<0.1	0.4	0.3	38	0.28	0.028
1429341	Soil	1.1	72.8	68.6	74	<0.1	33.8	15.5	350	3.65	11.7	1.6	0.9	10.4	20	<0.1	0.5	0.6	36	0.26	0.021
1429342	Soil	1.3	29.9	42.6	55	<0.1	29.0	16.1	409	3.55	24.3	1.0	1.9	7.6	21	<0.1	1.3	0.5	65	0.24	0.018
1429339	Soil	1.6	37.8	16.4	88	<0.1	27.3	13.3	530	4.89	6.9	1.7	1.7	8.7	18	<0.1	0.4	0.3	79	0.28	0.042
1429345	Soil	0.5	33.6	8.2	75	<0.1	20.6	16.5	643	4.20	8.5	0.9	3.1	4.0	25	<0.1	0.3	0.2	76	0.55	0.064
1429346	Soil	0.1	87.9	9.1	100	<0.1	25.3	27.7	750	5.79	20.7	0.3	1.8	1.2	17	<0.1	0.5	<0.1	132	0.57	0.052
1429349	Soil	0.7	20.4	13.8	48	<0.1	18.6	9.2	249	2.58	8.5	0.6	2.7	3.3	18	<0.1	0.4	0.2	54	0.25	0.024
1429348	Soil	1.2	19.0	20.0	50	0.1	17.1	11.6	730	2.17	18.9	0.7	1.0	3.2	24	0.2	1.3	0.2	44	0.33	0.039
1352839	Soil	0.7	32.4	5.2	77	<0.1	17.0	12.3	753	3.88	4.3	0.6	1.0	3.6	44	<0.1	0.4	0.2	93	0.89	0.223
1352838	Soil	0.4	77.0	3.9	105	<0.1	70.6	32.2	1271	6.75	10.2	0.7	1.4	3.5	40	<0.1	0.2	<0.1	170	1.16	0.242
1429347	Soil	0.5	31.4	10.5	69	<0.1	23.2	15.5	548	3.43	17.8	0.5	1.9	4.0	31	<0.1	0.7	0.1	62	0.85	0.051
1392848	Soil	1.0	17.8	10.2	51	0.1	20.3	10.9	341	2.96	8.6	0.4	<0.5	4.5	16	<0.1	0.4	0.1	56	0.25	0.022
1392847	Soil	0.6	27.9	17.3	85	<0.1	27.9	14.2	437	3.50	11.9	1.4	0.8	12.4	19	<0.1	0.7	<0.1	40	0.34	0.046
1429327	Soil	0.8	14.8	17.5	53	<0.1	19.7	10.5	454	2.83	6.0	0.6	0.6	6.4	19	<0.1	0.4	0.1	48	0.34	0.019



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 3 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1352834	Soil	66	33	0.59	485	0.110	2	1.83	0.009	0.58	0.1	0.07	7.1	0.4	<0.05	6	<0.5	<0.2
1352831	Soil	13	27	0.41	332	0.050	<1	1.21	0.014	0.05	0.1	0.04	4.2	<0.1	<0.05	4	<0.5	<0.2
1352836	Soil	12	83	1.24	217	0.125	<1	2.14	0.012	0.63	0.1	0.02	4.4	0.3	<0.05	6	<0.5	<0.2
1352833	Soil	12	30	0.45	230	0.053	<1	1.74	0.011	0.07	0.2	0.03	3.7	<0.1	<0.05	5	<0.5	<0.2
1352832	Soil	11	26	0.43	258	0.049	<1	1.36	0.011	0.04	0.1	0.03	4.0	<0.1	<0.05	4	<0.5	<0.2
1352837	Soil	9	25	0.36	306	0.037	2	1.37	0.009	0.13	0.2	0.04	3.7	<0.1	<0.05	4	<0.5	<0.2
1352828	Soil	19	27	0.26	241	0.027	3	1.37	0.005	0.11	<0.1	0.03	4.3	0.2	<0.05	5	<0.5	<0.2
1352827	Soil	13	27	0.32	240	0.039	1	1.30	0.007	0.11	0.1	0.02	3.5	0.1	<0.05	4	0.6	<0.2
1352826	Soil	12	29	0.44	286	0.052	<1	1.33	0.009	0.11	0.1	0.03	3.5	<0.1	<0.05	4	<0.5	<0.2
1352830	Soil	7	33	0.96	731	0.066	2	1.51	0.008	0.72	<0.1	0.05	18.8	0.3	<0.05	5	<0.5	<0.2
1352835	Soil	11	59	1.39	328	0.187	1	2.48	0.010	0.86	0.2	0.01	9.8	0.4	<0.05	11	0.7	<0.2
1429344	Soil	13	34	0.50	327	0.047	2	2.03	0.009	0.05	0.1	0.04	3.9	0.1	<0.05	5	0.9	<0.2
1429338	Soil	14	103	0.49	678	0.010	5	1.94	0.010	0.34	0.2	0.22	21.4	0.3	<0.05	6	<0.5	<0.2
1429337	Soil	15	33	0.32	315	0.020	4	1.18	0.013	0.07	0.2	0.33	9.4	0.1	<0.05	4	1.5	<0.2
1429336	Soil	14	30	0.43	476	0.040	2	1.43	0.018	0.05	0.2	0.06	5.0	<0.1	<0.05	4	1.0	<0.2
1429343	Soil	19	20	0.19	218	0.010	1	0.95	0.006	0.09	<0.1	0.14	6.8	<0.1	<0.05	3	1.1	<0.2
1429340	Soil	37	28	0.36	380	0.020	<1	1.42	0.008	0.22	<0.1	0.11	10.1	0.2	<0.05	5	<0.5	<0.2
1429341	Soil	29	23	0.25	351	0.010	3	1.12	0.009	0.14	<0.1	0.36	9.9	0.2	<0.05	4	0.8	<0.2
1429342	Soil	24	46	0.74	331	0.055	2	2.03	0.009	0.20	0.1	0.11	7.9	0.2	<0.05	6	0.5	<0.2
1429339	Soil	24	46	0.94	312	0.148	2	1.99	0.009	0.71	<0.1	0.02	11.0	0.4	<0.05	8	<0.5	<0.2
1429345	Soil	19	36	1.62	346	0.212	2	2.75	0.013	0.85	0.2	0.02	5.5	0.3	<0.05	7	<0.5	<0.2
1429346	Soil	6	33	2.31	612	0.186	<1	3.13	0.015	0.90	<0.1	0.08	12.4	0.4	<0.05	11	<0.5	<0.2
1429349	Soil	11	29	0.64	202	0.093	<1	1.33	0.010	0.31	0.2	0.02	5.0	0.2	<0.05	4	<0.5	<0.2
1429348	Soil	13	22	0.28	350	0.030	3	1.16	0.014	0.13	0.1	0.03	3.2	<0.1	<0.05	3	<0.5	<0.2
1352839	Soil	18	18	1.50	416	0.166	2	2.68	0.011	0.80	0.1	0.13	5.1	0.3	<0.05	8	<0.5	0.2
1352838	Soil	11	98	2.19	585	0.228	2	3.45	0.014	1.18	<0.1	0.02	12.8	0.3	<0.05	10	<0.5	<0.2
1429347	Soil	16	26	0.53	317	0.042	2	1.33	0.019	0.26	0.1	0.12	10.0	0.2	<0.05	5	0.5	<0.2
1392848	Soil	11	33	0.40	204	0.070	<1	1.77	0.014	0.15	0.2	0.03	3.6	0.1	<0.05	6	<0.5	<0.2
1392847	Soil	22	26	0.32	380	0.027	2	1.22	0.009	0.24	<0.1	0.05	7.4	0.2	<0.05	4	<0.5	<0.2
1429327	Soil	12	26	0.31	381	0.030	2	1.24	0.008	0.16	<0.1	0.03	5.3	0.1	<0.05	4	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 4 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	AQ201																				
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1392850	Soil	0.9	9.4	9.9	41	<0.1	14.2	6.7	225	2.13	6.8	0.4	2.3	3.1	14	<0.1	0.4	0.1	44	0.23	0.015
1429335	Soil	1.2	13.3	13.1	49	<0.1	15.3	6.1	152	2.71	16.2	0.5	6.4	3.0	13	<0.1	0.7	0.2	68	0.16	0.039
1429330	Soil	1.2	38.2	10.8	69	<0.1	42.2	15.4	533	3.86	5.3	1.1	1.7	7.3	31	<0.1	0.4	0.1	80	0.44	0.065
1429350	Soil	0.7	18.6	15.4	49	0.1	18.6	9.3	290	2.69	9.1	0.6	2.3	3.5	20	<0.1	0.5	0.2	61	0.30	0.022
1429329	Soil	1.5	46.0	11.4	93	<0.1	58.0	25.2	955	4.80	4.8	0.8	1.2	6.6	27	<0.1	0.3	<0.1	132	0.43	0.130
1429333	Soil	2.1	35.5	11.9	87	<0.1	49.9	15.9	442	3.88	6.9	0.9	<0.5	8.0	21	0.1	0.3	0.2	80	0.26	0.061
1429332	Soil	1.6	41.8	15.8	64	0.1	36.8	12.9	364	3.47	15.1	0.8	3.6	5.0	22	<0.1	1.0	0.2	68	0.21	0.054
1429331	Soil	1.0	21.0	13.9	50	<0.1	24.2	11.0	296	2.73	6.9	0.8	1.6	4.1	24	<0.1	0.4	<0.1	56	0.32	0.048
1429334	Soil	1.2	17.1	8.2	57	<0.1	22.6	8.8	357	2.75	12.5	0.6	3.6	3.4	21	0.1	0.4	0.1	55	0.30	0.052
1429328	Soil	0.8	19.8	8.0	49	<0.1	29.2	10.5	275	2.86	6.1	0.6	1.9	4.6	21	<0.1	0.4	<0.1	52	0.32	0.036
1392840	Soil	1.0	36.8	8.8	54	<0.1	41.9	13.2	404	3.05	13.3	0.8	1.9	6.1	37	<0.1	0.6	<0.1	63	0.53	0.059
1392828	Soil	0.8	23.4	11.7	57	<0.1	23.9	10.8	251	3.21	10.4	0.7	1.6	4.8	23	<0.1	0.7	0.1	59	0.32	0.046
1392830	Soil	1.1	34.9	25.0	75	<0.1	29.1	13.6	455	3.74	19.6	1.2	1.8	7.4	18	<0.1	0.9	0.2	53	0.35	0.045
1392846	Soil	1.0	26.5	22.0	141	<0.1	33.7	13.4	411	3.42	16.0	0.8	<0.5	8.5	28	0.3	0.9	0.1	43	0.34	0.050
1392849	Soil	0.9	15.4	16.1	68	<0.1	18.8	9.2	315	3.02	11.9	0.7	1.8	6.4	17	<0.1	0.4	0.1	39	0.25	0.022
1392839	Soil	1.2	21.9	9.8	54	<0.1	25.8	12.1	525	3.00	12.0	0.7	2.3	4.6	19	<0.1	0.7	0.1	55	0.22	0.019
1392844	Soil	0.8	34.3	11.9	69	0.1	36.0	12.4	427	3.01	9.0	1.3	3.5	6.0	63	0.2	0.7	0.1	51	0.78	0.101
1392838	Soil	1.0	20.5	16.6	61	0.1	20.6	13.3	1878	2.74	5.9	0.7	1.9	4.1	31	0.2	0.4	0.1	43	0.40	0.060
1392845	Soil	0.5	24.1	7.9	63	0.1	23.5	9.1	401	2.08	7.2	1.0	3.5	2.8	53	0.3	0.6	<0.1	37	1.21	0.069
1392837	Soil	3.3	24.0	10.7	71	<0.1	31.5	13.0	515	4.10	9.1	0.5	<0.5	4.2	17	<0.1	0.4	<0.1	82	0.29	0.032
1392843	Soil	1.2	31.0	13.3	70	0.1	32.2	12.4	444	3.07	8.6	1.3	3.0	6.2	62	0.2	0.6	0.1	55	0.73	0.105
1392841	Soil	1.3	51.1	14.4	68	<0.1	66.5	21.7	525	4.48	12.7	1.3	2.6	7.5	38	<0.1	0.8	0.1	69	0.56	0.086
1392827	Soil	1.1	20.7	14.9	75	<0.1	13.3	11.2	481	3.38	10.7	0.6	1.8	3.1	26	0.1	0.7	0.1	52	0.40	0.082
1392834	Soil	0.9	27.0	14.4	78	<0.1	21.1	12.2	458	3.75	6.6	0.9	1.7	5.7	25	<0.1	0.5	0.1	73	0.43	0.055
1392831	Soil	0.9	23.3	10.5	78	<0.1	14.0	12.2	426	3.95	9.4	0.6	0.8	4.4	16	<0.1	0.3	<0.1	77	0.28	0.053
1392836	Soil	0.7	17.3	12.0	56	<0.1	16.7	8.2	382	2.52	8.9	0.5	1.7	3.7	19	<0.1	0.5	0.2	49	0.31	0.034
1392833	Soil	1.2	19.5	9.3	109	<0.1	10.1	17.2	687	5.71	6.7	0.5	<0.5	4.3	11	<0.1	0.2	0.1	110	0.24	0.075
1392832	Soil	1.8	46.7	31.6	154	<0.1	42.9	19.6	1325	4.95	124.1	1.8	2.2	9.9	25	0.3	2.6	0.3	40	0.36	0.061
1392842	Soil	1.3	38.5	31.8	39	0.2	22.2	8.7	290	2.36	12.0	1.0	3.5	2.5	81	0.1	2.0	0.3	41	0.94	0.036
1392835	Soil	1.6	13.9	10.2	60	<0.1	17.7	7.7	314	3.05	12.5	0.4	3.7	3.5	12	<0.1	0.5	0.1	64	0.16	0.044



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 4 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1392850	Soil	9	24	0.38	327	0.039	<1	1.32	0.008	0.06	0.1	0.02	2.9	<0.1	<0.05	4	<0.5	<0.2
1429335	Soil	11	30	0.35	206	0.033	1	1.73	0.007	0.09	0.2	0.02	3.1	0.1	<0.05	6	<0.5	<0.2
1429330	Soil	22	58	0.58	455	0.057	2	1.66	0.011	0.20	<0.1	0.04	8.7	0.2	<0.05	6	<0.5	<0.2
1429350	Soil	11	31	0.61	224	0.096	2	1.43	0.012	0.36	0.2	0.03	5.0	0.2	<0.05	4	<0.5	<0.2
1429329	Soil	24	99	1.34	373	0.137	2	2.36	0.011	0.63	0.2	0.02	8.5	0.4	<0.05	9	<0.5	<0.2
1429333	Soil	29	64	0.68	256	0.077	1	1.81	0.008	0.29	0.1	0.01	5.6	0.3	<0.05	8	<0.5	<0.2
1429332	Soil	16	33	0.27	269	0.013	3	1.21	0.006	0.09	0.1	0.06	5.9	0.1	<0.05	4	0.8	<0.2
1429331	Soil	17	45	0.44	328	0.052	2	1.52	0.009	0.11	0.2	0.06	5.0	0.2	<0.05	6	0.6	<0.2
1429334	Soil	13	31	0.42	274	0.042	<1	1.34	0.009	0.08	0.2	0.04	3.5	0.1	<0.05	5	<0.5	<0.2
1429328	Soil	19	45	0.60	239	0.079	1	1.50	0.011	0.18	0.1	0.02	4.3	0.2	<0.05	5	<0.5	<0.2
1392840	Soil	25	51	0.55	452	0.059	2	1.45	0.019	0.12	0.2	0.08	7.7	0.1	<0.05	5	<0.5	<0.2
1392828	Soil	13	37	0.43	410	0.040	2	1.62	0.010	0.13	0.1	0.04	6.1	0.1	<0.05	6	<0.5	<0.2
1392830	Soil	20	31	0.43	553	0.054	2	1.34	0.012	0.19	0.1	0.09	10.0	0.2	<0.05	5	<0.5	<0.2
1392846	Soil	16	34	0.29	357	0.015	1	1.16	0.007	0.14	<0.1	0.07	6.5	0.1	<0.05	4	<0.5	<0.2
1392849	Soil	14	21	0.27	352	0.015	2	1.07	0.007	0.11	<0.1	0.03	3.8	0.1	<0.05	4	<0.5	<0.2
1392839	Soil	15	33	0.38	304	0.050	1	1.36	0.010	0.11	<0.1	0.03	4.6	0.1	<0.05	5	0.6	<0.2
1392844	Soil	26	39	0.58	528	0.062	2	1.42	0.021	0.17	0.2	0.09	7.1	0.1	<0.05	5	1.1	<0.2
1392838	Soil	17	24	0.30	519	0.042	2	1.29	0.014	0.23	<0.1	0.05	3.6	0.1	<0.05	5	<0.5	<0.2
1392845	Soil	14	21	0.39	458	0.032	2	0.99	0.015	0.07	0.1	0.07	3.8	<0.1	<0.05	3	<0.5	<0.2
1392837	Soil	10	54	0.74	452	0.102	1	1.80	0.011	0.61	<0.1	0.03	8.4	0.3	<0.05	7	<0.5	<0.2
1392843	Soil	25	37	0.51	467	0.055	3	1.35	0.016	0.17	0.2	0.09	6.6	0.1	<0.05	5	<0.5	<0.2
1392841	Soil	29	65	0.53	534	0.035	<1	1.43	0.016	0.20	0.1	0.07	11.8	0.2	<0.05	5	1.8	<0.2
1392827	Soil	10	24	0.31	420	0.015	2	1.11	0.008	0.16	<0.1	0.07	7.5	0.1	<0.05	4	0.6	<0.2
1392834	Soil	21	35	0.82	379	0.125	2	1.86	0.018	0.45	0.2	0.07	10.6	0.2	<0.05	7	0.9	<0.2
1392831	Soil	15	32	0.96	326	0.137	<1	1.96	0.011	0.56	<0.1	0.04	8.5	0.3	<0.05	7	0.8	<0.2
1392836	Soil	11	26	0.39	297	0.046	2	1.24	0.010	0.09	0.1	0.04	4.1	<0.1	<0.05	4	<0.5	<0.2
1392833	Soil	11	30	1.88	321	0.264	2	3.06	0.010	1.32	<0.1	0.01	10.9	0.6	<0.05	11	<0.5	<0.2
1392832	Soil	22	27	0.27	435	0.011	3	1.04	0.007	0.21	<0.1	0.23	14.6	0.2	<0.05	3	<0.5	<0.2
1392842	Soil	14	24	0.32	434	0.020	3	0.91	0.014	0.14	0.2	0.10	4.6	<0.1	<0.05	3	<0.5	<0.2
1392835	Soil	10	32	0.46	187	0.077	1	1.21	0.007	0.35	0.2	0.02	4.4	0.2	<0.05	6	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 5 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	AQ201																				
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1392829	Soil	0.9	24.6	12.7	55	<0.1	20.3	9.2	256	2.92	18.3	0.7	2.3	3.7	18	<0.1	0.8	0.1	50	0.27	0.045
1390450	Soil	0.7	33.5	20.5	48	0.1	24.4	14.8	580	2.83	15.1	1.9	2.7	3.8	34	0.1	0.9	0.2	52	1.01	0.058
1374678	Soil	1.6	39.0	33.8	97	0.2	35.6	17.0	634	4.54	17.2	1.7	8.4	6.9	29	0.2	0.6	0.5	70	0.68	0.089
1374679	Soil	1.0	31.6	22.6	66	0.2	24.3	12.3	740	2.47	14.0	2.6	2.0	3.5	48	0.3	0.8	0.3	39	1.44	0.062
1374677	Soil	1.8	14.9	33.3	45	0.1	14.2	7.0	236	2.01	9.8	0.7	2.9	2.1	19	0.1	0.8	0.4	53	0.28	0.032
1390448	Soil	0.3	34.4	15.8	81	<0.1	21.9	21.1	827	5.03	5.0	0.5	0.8	4.2	15	<0.1	0.2	0.1	94	0.48	0.059
1390449	Soil	0.8	35.5	27.5	53	0.2	27.3	14.8	660	2.66	18.0	1.9	3.8	3.6	37	0.2	1.1	0.3	46	1.12	0.066
1374676	Soil	1.1	16.9	38.9	55	<0.1	15.9	10.7	305	2.79	20.2	0.7	2.2	2.8	28	0.2	1.0	0.3	55	0.53	0.040
1390446	Soil	1.5	58.6	112.9	102	0.1	39.5	12.9	469	4.08	37.0	1.8	2.5	10.3	25	<0.1	2.6	1.6	69	0.22	0.072
1390447	Soil	0.7	28.1	10.9	93	<0.1	29.1	19.6	1196	4.86	5.2	0.5	2.0	5.1	24	0.1	0.5	<0.1	81	0.74	0.062
1390445	Soil	2.2	42.8	29.4	104	<0.1	38.6	13.6	542	4.23	199.1	1.4	0.6	7.1	27	0.1	10.7	0.3	45	0.14	0.052
1390444	Soil	1.3	48.6	31.2	140	<0.1	47.5	14.6	442	4.60	63.0	2.8	1.8	14.5	22	<0.1	2.0	0.3	38	0.24	0.059
1390443	Soil	1.6	81.6	15.3	194	<0.1	56.0	19.6	620	5.83	18.7	2.9	4.3	15.5	19	0.1	0.7	0.2	41	0.35	0.073
1390442	Soil	1.7	46.6	73.8	129	<0.1	40.2	12.6	443	4.72	38.1	1.9	2.6	12.5	19	0.2	1.3	0.7	59	0.19	0.046
1390441	Soil	1.6	42.1	35.7	119	<0.1	36.5	11.9	335	3.85	41.2	1.4	2.4	8.6	19	0.1	1.9	0.4	59	0.18	0.045
1390440	Soil	1.5	20.0	37.2	70	<0.1	22.7	8.8	446	2.74	9.8	0.8	0.9	4.8	18	0.1	1.0	0.3	58	0.29	0.040
1390439	Soil	1.6	53.3	23.7	93	<0.1	35.0	12.7	422	4.06	36.8	1.6	3.2	9.0	19	<0.1	0.7	0.3	76	0.36	0.049
1390438	Soil	1.3	41.4	35.7	120	<0.1	35.5	11.3	348	3.77	32.2	2.6	4.2	9.6	17	<0.1	1.0	0.6	39	0.22	0.050
1390437	Soil	1.7	34.8	44.2	85	<0.1	29.2	11.0	424	3.52	18.3	1.4	3.2	6.8	20	<0.1	1.0	0.4	59	0.27	0.042
1390436	Soil	0.8	16.3	13.9	47	<0.1	19.6	6.7	200	2.22	11.5	0.5	0.7	3.5	23	<0.1	0.6	0.1	50	0.31	0.044
1390435	Soil	1.8	42.5	51.2	123	<0.1	40.5	13.2	386	4.35	55.1	2.3	2.3	11.7	18	<0.1	2.4	0.6	42	0.24	0.054
1390434	Soil	1.5	46.1	23.3	92	<0.1	24.0	15.5	534	5.27	26.2	1.4	2.0	4.8	16	<0.1	0.9	0.4	85	0.32	0.079
1390433	Soil	2.2	49.7	44.1	59	<0.1	33.0	12.3	451	3.68	22.0	1.6	1.5	12.9	23	<0.1	1.0	0.5	43	0.35	0.038
1390432	Soil	1.6	25.2	32.2	55	<0.1	29.4	12.2	413	3.32	14.0	1.2	2.8	7.4	21	<0.1	0.7	0.3	60	0.43	0.046
1390431	Soil	1.2	15.8	22.7	63	<0.1	35.9	11.1	273	3.37	8.4	0.8	1.4	6.6	20	<0.1	0.5	0.3	57	0.46	0.056
1390430	Soil	1.6	38.7	36.1	103	0.1	33.1	15.6	668	4.54	21.2	1.3	2.5	8.3	23	0.2	1.4	0.4	67	0.59	0.056
1390429	Soil	0.8	24.8	19.2	62	0.1	24.7	11.4	564	2.80	14.9	2.0	3.3	4.1	52	0.2	0.7	0.2	38	1.40	0.068
1390428	Soil	1.3	18.7	23.6	67	0.1	19.0	13.0	794	2.87	18.5	1.8	1.9	4.1	42	0.2	1.2	0.2	46	1.04	0.060
1390427	Soil	0.8	24.8	38.5	51	0.2	23.0	10.0	452	2.63	41.9	2.3	2.3	4.2	45	0.2	1.9	0.4	44	0.90	0.050
1390426	Soil	1.3	15.1	21.9	52	<0.1	17.0	8.7	700	2.60	16.4	1.0	1.8	3.4	22	0.1	0.8	0.3	51	0.32	0.024



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 5 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1392829	Soil	12	29	0.38	308	0.036	2	1.25	0.009	0.10	0.1	0.04	5.9	0.1	<0.05	4	0.6	<0.2
1390450	Soil	27	28	0.42	598	0.038	2	1.30	0.014	0.21	0.1	0.18	10.9	0.1	<0.05	4	0.8	<0.2
1374678	Soil	25	54	0.73	568	0.064	2	2.11	0.009	0.50	0.1	0.12	9.7	0.4	<0.05	8	0.5	<0.2
1374679	Soil	20	23	0.30	663	0.019	3	1.16	0.013	0.12	0.1	0.20	7.5	0.1	<0.05	4	0.6	<0.2
1374677	Soil	11	28	0.30	300	0.045	3	1.03	0.012	0.16	0.2	0.06	4.0	<0.1	<0.05	5	<0.5	<0.2
1390448	Soil	14	43	1.30	596	0.137	3	2.24	0.011	1.08	0.1	0.03	18.2	0.4	<0.05	7	<0.5	<0.2
1390449	Soil	34	28	0.41	639	0.033	2	1.33	0.015	0.19	0.2	0.22	11.4	0.1	<0.05	4	0.9	<0.2
1374676	Soil	12	29	0.35	299	0.047	2	1.05	0.013	0.19	0.1	0.06	6.0	0.1	<0.05	4	<0.5	<0.2
1390446	Soil	17	36	0.18	243	0.011	2	0.87	0.008	0.10	0.1	0.04	10.2	0.1	<0.05	3	1.1	<0.2
1390447	Soil	19	63	0.60	829	0.074	2	1.40	0.015	0.44	<0.1	0.04	19.0	0.2	<0.05	5	<0.5	<0.2
1390445	Soil	20	29	0.17	165	0.007	<1	0.86	0.004	0.10	0.1	0.13	5.4	0.1	<0.05	2	0.8	<0.2
1390444	Soil	33	23	0.18	229	0.006	<1	0.77	0.005	0.12	<0.1	0.10	9.7	0.1	<0.05	3	0.9	<0.2
1390443	Soil	42	27	0.23	294	0.006	<1	0.97	0.009	0.15	<0.1	0.06	10.9	0.2	<0.05	3	0.9	<0.2
1390442	Soil	26	34	0.38	282	0.068	1	1.29	0.008	0.45	<0.1	0.06	7.4	0.4	<0.05	5	0.6	<0.2
1390441	Soil	18	31	0.32	280	0.030	<1	1.24	0.010	0.22	0.1	0.01	5.8	0.2	<0.05	5	0.8	<0.2
1390440	Soil	12	27	0.33	308	0.043	1	1.25	0.010	0.16	0.1	0.01	3.9	0.2	<0.05	4	<0.5	<0.2
1390439	Soil	20	39	0.61	320	0.097	<1	1.70	0.013	0.49	0.1	0.04	8.1	0.4	<0.05	7	0.9	<0.2
1390438	Soil	15	25	0.26	288	0.016	<1	0.98	0.007	0.20	<0.1	0.02	6.3	0.2	<0.05	4	<0.5	<0.2
1390437	Soil	18	31	0.35	411	0.037	<1	1.22	0.011	0.21	0.1	0.04	6.6	0.2	<0.05	4	<0.5	<0.2
1390436	Soil	11	26	0.45	216	0.061	<1	1.23	0.014	0.09	0.1	0.02	3.4	<0.1	<0.05	4	0.7	<0.2
1390435	Soil	27	23	0.23	333	0.010	1	1.03	0.006	0.16	<0.1	0.04	6.2	0.2	<0.05	3	0.9	<0.2
1390434	Soil	12	35	0.38	364	0.019	1	1.38	0.007	0.30	<0.1	0.03	15.8	0.2	<0.05	5	0.7	<0.2
1390433	Soil	31	25	0.21	682	0.004	1	1.29	0.006	0.17	<0.1	0.09	10.0	0.2	<0.05	4	0.9	<0.2
1390432	Soil	32	36	0.55	390	0.027	<1	1.65	0.010	0.20	0.1	0.04	9.2	0.2	<0.05	5	<0.5	<0.2
1390431	Soil	18	73	0.56	301	0.047	1	1.60	0.010	0.26	0.1	0.01	5.5	0.2	<0.05	6	<0.5	<0.2
1390430	Soil	22	35	0.37	339	0.016	<1	1.25	0.010	0.20	<0.1	0.05	11.1	0.1	<0.05	4	0.7	<0.2
1390429	Soil	25	29	0.46	468	0.037	<1	1.27	0.014	0.16	0.1	0.11	7.2	0.1	0.05	4	0.8	<0.2
1390428	Soil	17	31	0.43	348	0.034	2	1.25	0.014	0.14	0.1	0.11	6.4	0.1	<0.05	4	<0.5	<0.2
1390427	Soil	18	23	0.31	432	0.023	3	1.18	0.014	0.12	0.2	0.17	6.1	0.1	<0.05	3	0.6	<0.2
1390426	Soil	14	28	0.37	338	0.049	1	1.36	0.012	0.17	0.1	0.03	3.6	<0.1	<0.05	4	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 6 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	Unit	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%
		MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL
1335738	Soil	1.7	33.5	45.6	127	<0.1	25.4	10.3	268	3.27	27.5	1.4	1.1	8.0	17	0.2	4.0	0.4	55	0.21	0.060
1335739	Soil	1.1	23.7	17.3	60	<0.1	29.2	10.3	431	2.86	11.8	0.8	4.3	4.4	26	<0.1	0.7	0.4	55	0.39	0.073
1335737	Soil	2.0	52.0	17.0	121	<0.1	40.9	13.7	429	4.38	13.2	1.4	0.9	12.2	18	<0.1	0.9	0.2	38	0.26	0.047
1335736	Soil	1.4	28.4	29.7	106	<0.1	32.8	12.9	328	3.94	9.8	1.2	1.0	8.9	16	0.1	0.6	0.3	46	0.23	0.034
1335734	Soil	1.2	20.5	10.9	64	<0.1	23.5	9.5	228	3.08	11.3	0.6	1.3	5.0	15	0.1	0.6	0.2	56	0.26	0.044
1335735	Soil	1.7	37.7	15.3	118	<0.1	41.5	15.4	359	4.65	29.2	1.9	0.8	10.3	16	0.1	1.0	0.1	43	0.21	0.039
1335733	Soil	0.9	116.0	7.0	83	<0.1	25.3	21.1	1592	5.92	2.2	1.0	1.7	5.2	21	<0.1	0.7	<0.1	92	0.54	0.056
1335732	Soil	0.6	35.4	11.1	101	<0.1	17.9	24.9	1497	6.67	3.7	0.8	1.0	5.8	20	<0.1	0.5	0.2	109	0.50	0.070
1335730	Soil	0.8	25.9	25.0	53	0.2	20.0	9.5	367	2.64	14.0	1.5	3.0	3.9	29	<0.1	0.9	0.3	50	0.55	0.055
1335731	Soil	0.5	40.3	20.8	71	0.1	22.9	18.3	758	4.16	6.0	0.6	1.2	3.4	23	0.1	0.7	0.2	72	0.55	0.062
1335728	Soil	1.2	34.7	21.9	71	0.1	26.5	10.6	386	3.30	15.1	1.3	1.5	5.9	26	0.1	0.8	0.3	54	0.58	0.056
1335729	Soil	1.1	31.7	50.1	56	0.1	23.2	9.2	237	2.75	21.7	1.8	3.2	6.0	32	<0.1	1.5	0.6	45	0.31	0.036
1335726	Soil	0.8	34.0	10.5	77	0.1	23.8	13.2	560	3.11	7.6	1.5	2.5	2.2	54	0.4	0.5	0.1	66	1.65	0.092
1335727	Soil	0.9	62.6	10.2	76	0.2	33.2	16.8	801	3.31	7.1	1.6	1.4	2.3	47	0.3	0.5	0.1	85	1.53	0.132
1335928	Soil	1.9	39.6	12.7	86	0.2	35.3	11.7	475	2.78	15.6	1.0	1.9	2.1	77	1.8	0.7	0.2	71	1.95	0.147
1335929	Soil	1.6	53.5	9.7	96	0.2	34.3	20.6	663	4.78	14.2	0.7	1.6	2.5	44	0.4	0.6	0.1	105	1.43	0.137
1335927	Soil	1.3	23.7	18.6	63	<0.1	23.3	9.2	299	2.97	17.5	1.3	1.8	5.4	21	<0.1	0.9	0.2	51	0.34	0.048
1335926	Soil	1.4	25.7	28.1	66	0.2	20.2	10.9	689	2.91	9.2	1.9	2.7	6.8	27	0.1	0.5	0.3	55	0.47	0.039
1335750	Soil	1.1	26.9	14.2	51	<0.1	23.6	10.5	236	2.63	13.0	1.1	3.8	4.7	22	0.1	0.8	0.2	56	0.30	0.035
1335749	Soil	1.6	18.2	19.6	45	<0.1	18.5	8.9	218	2.72	15.3	0.5	<0.5	1.5	15	<0.1	0.7	0.2	56	0.17	0.042
1335748	Soil	1.0	39.2	23.6	50	<0.1	28.0	11.4	380	2.55	12.5	1.5	2.7	5.1	27	0.1	1.0	0.3	57	0.39	0.034
1335747	Soil	0.9	14.5	11.4	51	<0.1	20.1	10.2	217	2.67	11.2	0.8	0.6	3.4	24	<0.1	0.6	0.1	56	0.46	0.050
1335746	Soil	1.0	29.5	20.7	74	<0.1	18.6	12.6	416	4.00	6.2	0.8	1.0	6.7	15	<0.1	0.5	0.2	69	0.28	0.057
1335745	Soil	1.2	18.9	9.3	69	<0.1	16.3	15.9	620	3.65	8.4	0.4	<0.5	2.7	13	<0.1	0.4	<0.1	80	0.23	0.026
1335744	Soil	0.5	49.6	8.0	64	0.1	33.2	16.0	687	3.38	10.3	0.5	1.5	4.0	26	<0.1	0.5	<0.1	74	0.93	0.054
1335740	Soil	0.7	33.9	13.6	52	<0.1	30.4	10.2	320	2.78	17.0	0.7	10.7	5.2	25	<0.1	0.8	0.1	60	0.41	0.043
1335743	Soil	1.3	23.4	8.8	77	<0.1	17.8	11.9	411	3.83	7.7	0.6	<0.5	4.6	15	<0.1	0.5	0.1	67	0.27	0.036
1335742	Soil	0.7	36.8	10.0	56	<0.1	36.9	11.3	426	2.66	12.1	0.7	3.9	5.2	27	<0.1	0.9	0.1	51	0.42	0.036
1335741	Soil	0.7	32.8	15.1	51	0.1	26.2	9.6	336	2.50	12.2	0.5	5.1	4.4	27	<0.1	0.8	0.1	52	0.41	0.043
1385480	Soil	1.3	45.9	12.6	80	0.2	57.0	20.3	1058	3.39	9.2	1.7	0.8	4.0	79	0.2	0.5	0.1	64	1.22	0.095

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 6 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1335738	Soil	18	23	0.25	265	0.026	<1	0.88	0.007	0.20	<0.1	0.02	5.3	0.1	<0.05	3	<0.5	<0.2
1335739	Soil	15	35	0.46	281	0.061	2	1.48	0.011	0.16	0.1	0.02	6.1	<0.1	<0.05	4	<0.5	<0.2
1335737	Soil	28	22	0.23	272	0.011	1	0.93	0.006	0.10	<0.1	0.02	5.3	<0.1	<0.05	3	1.1	<0.2
1335736	Soil	19	28	0.33	172	0.030	1	1.12	0.008	0.12	0.1	0.02	5.0	0.1	<0.05	4	0.8	<0.2
1335734	Soil	12	28	0.38	187	0.038	<1	1.34	0.008	0.09	0.1	0.02	3.6	<0.1	<0.05	4	0.6	<0.2
1335735	Soil	27	25	0.25	237	0.012	1	0.98	0.005	0.10	<0.1	0.05	6.4	0.1	<0.05	3	1.1	<0.2
1335733	Soil	19	45	0.58	724	0.030	<1	1.52	0.008	0.53	<0.1	0.11	25.0	0.3	<0.05	5	<0.5	<0.2
1335732	Soil	19	24	1.29	682	0.142	1	2.55	0.010	1.09	0.1	0.06	22.0	0.4	<0.05	9	<0.5	<0.2
1335730	Soil	14	30	0.39	531	0.033	1	1.45	0.013	0.07	0.2	0.23	7.4	<0.1	<0.05	4	<0.5	<0.2
1335731	Soil	15	30	0.54	410	0.049	2	1.23	0.011	0.33	0.1	0.19	15.6	0.2	<0.05	4	<0.5	<0.2
1335728	Soil	19	32	0.42	538	0.040	2	1.50	0.016	0.16	0.1	0.20	9.7	0.1	<0.05	5	0.7	<0.2
1335729	Soil	15	28	0.31	332	0.029	<1	1.16	0.012	0.08	0.1	0.29	7.1	<0.1	<0.05	4	<0.5	<0.2
1335726	Soil	16	29	0.57	490	0.031	2	1.45	0.015	0.11	0.1	0.11	8.2	<0.1	<0.05	5	0.8	<0.2
1335727	Soil	22	37	0.81	636	0.042	2	1.74	0.019	0.14	0.1	0.13	12.1	<0.1	<0.05	5	1.5	<0.2
1335928	Soil	19	29	0.42	554	0.030	3	1.23	0.014	0.12	0.2	0.16	6.6	<0.1	<0.05	4	1.5	<0.2
1335929	Soil	14	39	0.98	554	0.062	2	1.89	0.015	0.35	0.1	0.28	15.8	0.2	<0.05	6	0.7	<0.2
1335927	Soil	21	32	0.39	383	0.032	2	1.33	0.010	0.09	0.1	0.16	6.4	<0.1	<0.05	4	<0.5	<0.2
1335926	Soil	33	34	0.41	649	0.028	<1	1.71	0.010	0.10	0.1	0.19	10.7	<0.1	<0.05	5	0.8	<0.2
1335750	Soil	17	32	0.46	418	0.045	1	1.57	0.011	0.06	0.2	0.17	4.9	<0.1	<0.05	5	<0.5	<0.2
1335749	Soil	10	26	0.34	180	0.030	1	1.43	0.010	0.05	0.1	0.06	3.0	<0.1	<0.05	5	<0.5	<0.2
1335748	Soil	22	32	0.42	383	0.073	<1	1.78	0.017	0.07	0.1	0.22	7.4	<0.1	<0.05	5	0.6	<0.2
1335747	Soil	13	30	0.47	334	0.045	<1	1.54	0.015	0.06	0.3	0.04	3.8	<0.1	<0.05	5	<0.5	<0.2
1335746	Soil	23	26	0.59	239	0.084	1	1.59	0.009	0.39	0.1	0.02	9.2	0.2	<0.05	6	<0.5	<0.2
1335745	Soil	6	31	0.89	208	0.131	<1	1.87	0.009	0.51	0.1	0.01	4.8	0.3	<0.05	7	<0.5	<0.2
1335744	Soil	17	51	0.94	438	0.094	<1	1.69	0.023	0.28	0.2	0.08	11.4	0.2	<0.05	5	<0.5	<0.2
1335740	Soil	18	32	0.48	265	0.071	2	1.29	0.018	0.13	0.2	0.03	5.5	<0.1	<0.05	4	<0.5	<0.2
1335743	Soil	13	26	0.37	241	0.042	<1	1.27	0.009	0.18	0.1	0.02	9.1	<0.1	<0.05	4	<0.5	<0.2
1335742	Soil	20	31	0.53	477	0.076	2	1.50	0.026	0.08	0.2	0.06	6.4	<0.1	<0.05	4	<0.5	<0.2
1335741	Soil	16	29	0.47	280	0.065	1	1.12	0.019	0.08	0.1	0.05	5.4	<0.1	<0.05	3	<0.5	<0.2
1385480	Soil	28	60	0.64	584	0.027	2	1.65	0.012	0.24	<0.1	0.20	9.3	0.2	<0.05	5	0.8	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 7 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte Unit MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	2	0.01	0.001	
1385481	Soil	1.4	43.3	13.1	83	0.1	55.7	19.7	785	3.48	10.7	1.5	4.0	4.7	74	0.3	0.6	0.2	63	1.15	0.104
1385482	Soil	1.0	48.5	10.3	69	0.2	84.0	24.9	716	4.17	22.8	1.1	<0.5	5.7	72	0.2	0.6	<0.1	87	1.05	0.102
1385483	Soil	1.6	50.5	15.2	85	0.1	67.8	20.7	563	3.95	40.9	1.0	1.2	6.1	36	0.2	1.1	0.1	83	0.41	0.080
1385479	Soil	1.1	40.6	14.8	82	0.1	63.5	17.7	558	3.68	11.3	1.3	1.4	5.3	43	0.1	0.4	0.2	69	0.59	0.085
1385478	Soil	1.5	60.1	16.0	109	0.1	61.5	24.9	776	4.92	12.9	1.4	2.1	8.2	32	0.3	0.3	0.2	111	0.48	0.103
1385477	Soil	1.5	106.0	21.5	107	0.1	106.1	36.8	1025	7.45	12.8	1.4	4.1	9.2	45	0.2	0.2	0.2	195	0.79	0.160
1385476	Soil	1.9	62.1	25.0	110	<0.1	52.4	21.2	628	4.76	8.5	1.6	2.2	9.7	31	0.1	0.4	0.3	73	0.41	0.086
1385497	Soil	0.9	16.0	11.0	46	<0.1	16.4	7.8	207	2.44	14.9	0.8	1.6	4.8	16	<0.1	0.6	0.1	48	0.16	0.030
1385498	Soil	0.9	20.1	15.2	63	<0.1	23.3	9.8	292	3.19	22.3	1.0	5.3	10.4	17	<0.1	0.5	0.2	51	0.19	0.031
1385500	Soil	1.5	35.0	11.1	83	<0.1	34.7	10.4	245	3.31	17.9	0.9	2.5	4.6	19	<0.1	1.3	0.1	49	0.20	0.049
1385496	Soil	1.2	18.4	13.4	53	<0.1	17.6	7.8	270	2.50	30.3	0.7	5.9	5.1	18	<0.1	0.6	0.1	42	0.19	0.034
1385494	Soil	1.3	25.3	15.6	61	0.1	22.5	9.9	299	3.04	9.3	0.9	4.7	5.5	26	0.1	0.4	0.2	47	0.26	0.023
1385493	Soil	1.3	25.2	15.7	64	<0.1	23.2	10.5	353	3.30	11.0	1.0	1.5	6.6	24	<0.1	0.4	0.2	45	0.24	0.027
1385499	Soil	1.3	21.2	13.5	57	<0.1	22.4	7.4	213	2.74	14.1	0.8	1.3	3.5	20	<0.1	0.7	0.2	57	0.21	0.043
1385495	Soil	0.9	43.1	28.8	126	0.3	21.5	15.4	650	4.85	19.1	1.1	2.7	5.0	70	0.3	0.6	0.2	58	0.72	0.058
1385484	Soil	1.3	32.1	18.9	62	0.3	30.8	22.4	1156	2.99	29.7	1.2	2.6	3.2	29	0.2	0.6	0.2	55	0.30	0.047
1385492	Soil	1.5	34.4	15.2	86	<0.1	38.0	16.6	459	4.39	29.0	1.4	1.3	11.6	26	<0.1	0.4	0.2	56	0.24	0.044
1385491	Soil	1.2	31.7	18.6	80	0.2	29.1	14.4	710	3.47	18.9	2.4	1.9	9.0	64	0.3	0.6	0.2	47	0.76	0.056
1385490	Soil	0.8	21.9	9.6	70	<0.1	26.8	9.7	391	2.94	7.7	1.1	2.6	4.3	53	0.2	0.6	0.2	53	0.63	0.043
1385489	Soil	0.5	36.5	9.4	64	<0.1	30.9	11.7	441	2.71	15.3	0.6	5.5	4.8	76	0.1	0.6	0.1	48	1.86	0.078
1385488	Soil	0.5	32.6	12.5	76	0.1	30.0	12.3	549	3.28	12.2	0.9	2.5	8.3	46	0.1	0.6	0.1	51	0.74	0.066
1385487	Soil	0.7	40.1	16.4	53	0.1	25.8	10.2	557	2.63	7.7	2.1	4.1	4.4	83	0.1	0.4	0.1	36	1.61	0.063
1385486	Soil	0.5	18.8	10.7	59	<0.1	20.7	9.0	381	2.39	8.6	0.9	1.3	4.4	60	<0.1	0.4	0.1	42	1.09	0.066
1385485	Soil	0.9	20.5	9.8	95	<0.1	35.2	16.6	1037	2.92	15.5	0.8	2.1	3.9	81	0.2	0.4	<0.1	54	1.15	0.069
1390379	Soil	4.2	87.7	28.4	226	<0.1	60.4	17.0	996	5.08	21.5	1.7	1.7	9.2	20	0.4	1.2	0.2	66	0.21	0.059
1417581	Soil	2.9	46.9	21.3	85	0.2	13.5	11.6	366	4.01	21.6	1.0	2.9	4.0	33	<0.1	1.5	0.1	52	0.28	0.049
1417582	Soil	0.9	28.3	10.5	67	<0.1	20.1	9.6	489	3.00	14.3	0.9	5.7	5.0	30	<0.1	0.6	0.1	52	0.40	0.048
1417594	Soil	1.7	77.3	45.8	235	0.2	50.4	20.0	1306	4.92	11.9	1.4	4.4	12.0	32	0.5	0.5	0.2	81	0.61	0.105
1417587	Soil	1.1	61.5	17.5	122	0.1	48.7	18.3	831	4.08	11.1	1.0	2.0	8.6	31	0.3	0.6	0.2	83	0.61	0.086
1417590	Soil	2.0	50.6	22.4	104	0.1	42.7	16.6	1036	4.03	23.0	1.3	3.3	9.9	28	0.4	0.7	0.2	49	0.46	0.096



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 7 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1385481	Soil	24	60	0.62	477	0.031	<1	1.41	0.011	0.23	0.1	0.19	9.3	0.2	<0.05	4	1.0	<0.2
1385482	Soil	35	108	1.19	581	0.058	<1	1.89	0.014	0.34	<0.1	0.11	11.2	0.3	<0.05	6	0.8	<0.2
1385483	Soil	22	75	0.86	419	0.044	2	1.50	0.010	0.25	0.1	0.11	9.0	0.3	<0.05	5	0.6	<0.2
1385479	Soil	23	61	0.61	461	0.050	<1	1.40	0.010	0.26	0.1	0.10	8.9	0.3	<0.05	5	<0.5	<0.2
1385478	Soil	28	78	0.97	441	0.110	1	1.90	0.011	0.62	<0.1	0.12	12.6	0.4	<0.05	7	<0.5	<0.2
1385477	Soil	44	151	1.31	703	0.067	1	2.08	0.008	0.82	<0.1	0.19	29.5	0.4	<0.05	7	<0.5	<0.2
1385476	Soil	27	61	0.65	381	0.060	<1	1.67	0.008	0.46	<0.1	0.13	11.7	0.3	<0.05	6	<0.5	<0.2
1385497	Soil	17	27	0.37	285	0.055	2	1.30	0.008	0.11	0.1	0.04	3.3	0.1	<0.05	4	<0.5	<0.2
1385498	Soil	29	34	0.48	233	0.077	2	1.53	0.008	0.27	0.1	0.03	5.4	0.2	<0.05	6	<0.5	<0.2
1385500	Soil	15	27	0.32	391	0.022	2	1.21	0.006	0.10	0.1	0.07	4.1	0.1	<0.05	4	<0.5	<0.2
1385496	Soil	14	20	0.26	262	0.022	2	0.94	0.006	0.11	<0.1	0.04	3.2	0.1	<0.05	4	<0.5	<0.2
1385494	Soil	14	24	0.33	390	0.027	3	1.10	0.007	0.20	0.1	0.04	5.0	0.1	<0.05	4	<0.5	<0.2
1385493	Soil	17	24	0.37	409	0.023	3	1.21	0.008	0.16	<0.1	0.05	6.8	0.1	<0.05	4	<0.5	<0.2
1385499	Soil	14	27	0.34	416	0.030	2	1.38	0.007	0.10	0.1	0.04	3.6	0.1	<0.05	5	<0.5	<0.2
1385495	Soil	13	31	0.43	480	0.013	3	1.07	0.010	0.21	<0.1	0.35	24.6	0.2	<0.05	3	0.6	<0.2
1385484	Soil	21	33	0.35	552	0.018	2	1.41	0.007	0.15	0.1	0.13	5.3	0.2	<0.05	5	<0.5	<0.2
1385492	Soil	21	41	0.83	252	0.116	1	1.81	0.009	0.44	<0.1	0.10	6.9	0.4	<0.05	6	<0.5	<0.2
1385491	Soil	20	32	0.67	403	0.063	3	1.41	0.014	0.30	0.1	0.17	7.1	0.3	<0.05	5	0.5	<0.2
1385490	Soil	15	31	0.57	342	0.078	2	1.39	0.012	0.19	0.2	0.08	7.1	0.2	<0.05	5	<0.5	<0.2
1385489	Soil	16	29	0.77	307	0.077	2	1.18	0.023	0.18	0.2	0.09	4.6	0.1	<0.05	4	<0.5	<0.2
1385488	Soil	22	33	0.76	305	0.108	2	1.35	0.021	0.28	0.2	0.04	5.6	0.2	<0.05	5	<0.5	<0.2
1385487	Soil	24	23	0.43	363	0.039	4	0.96	0.016	0.17	0.1	0.14	6.0	0.1	<0.05	3	0.7	<0.2
1385486	Soil	14	24	0.48	248	0.056	2	1.05	0.020	0.13	0.2	0.06	4.7	0.1	<0.05	3	<0.5	<0.2
1385485	Soil	20	46	0.63	487	0.045	3	1.14	0.012	0.22	0.1	0.17	6.0	0.2	0.06	4	<0.5	<0.2
1390379	Soil	14	37	0.12	365	0.003	<1	0.76	0.003	0.12	<0.1	0.22	9.5	0.1	<0.05	2	1.2	<0.2
1417581	Soil	11	20	0.20	460	0.010	<1	0.79	0.014	0.09	<0.1	0.33	14.7	0.2	<0.05	2	<0.5	<0.2
1417582	Soil	15	30	0.37	823	0.050	2	1.35	0.014	0.12	0.1	0.19	9.2	0.1	<0.05	4	<0.5	<0.2
1417594	Soil	18	64	0.80	596	0.114	2	1.63	0.012	0.65	0.1	0.10	12.1	0.4	<0.05	7	<0.5	<0.2
1417587	Soil	21	66	0.75	520	0.080	1	1.74	0.016	0.40	0.1	0.07	12.7	0.3	<0.05	6	<0.5	<0.2
1417590	Soil	25	30	0.42	378	0.037	1	1.03	0.012	0.24	0.2	0.09	7.5	0.2	<0.05	4	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 8 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte	AQ201																				
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1390381	Soil	1.7	35.6	56.4	94	0.1	27.0	10.2	486	3.31	12.5	1.1	3.5	7.1	25	0.1	0.7	0.7	49	0.23	0.062
1417593	Soil	1.2	61.6	11.5	88	<0.1	44.4	16.7	762	3.56	21.1	0.8	2.5	4.4	40	0.2	0.8	0.2	72	0.70	0.070
1390380	Soil	3.0	98.4	25.3	186	<0.1	51.6	20.4	608	4.41	5.8	2.2	2.4	15.5	27	0.1	0.3	0.3	63	0.34	0.101
1417595	Soil	2.1	89.9	32.2	155	0.2	82.7	30.8	1350	5.57	9.8	1.0	2.1	7.7	63	0.4	0.8	0.3	102	1.21	0.083
1417597	Soil	1.1	32.0	18.6	55	<0.1	32.4	12.5	601	2.68	10.0	1.5	2.7	2.9	106	0.1	0.8	0.1	40	1.31	0.091
1417588	Soil	1.0	29.4	14.6	71	0.1	25.8	13.2	431	3.20	11.7	1.2	2.1	4.4	37	0.1	0.8	0.5	63	0.59	0.050
1417598	Soil	1.0	32.7	11.1	68	<0.1	33.6	12.6	585	2.70	9.1	1.4	3.6	4.0	90	0.2	0.7	0.1	50	1.05	0.091
1390377	Soil	0.6	25.8	11.1	51	0.6	33.0	7.6	738	1.27	4.6	0.7	2.0	1.9	108	0.8	0.5	0.1	24	1.67	0.069
1417584	Soil	1.2	21.8	13.6	75	<0.1	20.7	10.6	576	3.45	13.5	0.8	4.4	6.3	25	0.1	0.6	0.1	56	0.38	0.061
1417596	Soil	0.6	42.8	26.6	94	0.1	36.9	16.4	602	4.16	16.8	1.6	3.9	15.2	58	<0.1	0.9	0.2	39	1.42	0.067
1417589	Soil	1.1	65.6	15.3	84	<0.1	44.0	22.6	918	4.75	10.5	0.9	2.7	6.9	24	0.1	0.6	0.1	87	0.62	0.071
1417585	Soil	1.4	42.8	12.7	135	<0.1	18.3	15.6	986	5.71	15.6	1.3	2.0	9.4	22	0.2	0.6	0.2	60	0.47	0.107
1417592	Soil	1.6	75.5	15.8	142	<0.1	63.9	22.0	1114	4.97	23.0	1.3	1.1	8.5	23	0.2	0.5	0.2	113	0.63	0.122
1390378	Soil	2.8	72.6	39.7	181	0.2	70.8	16.7	841	4.07	16.7	2.0	7.2	11.1	36	0.7	2.1	0.5	58	0.59	0.178
1390382	Soil	1.3	93.4	14.1	107	0.2	75.9	32.6	1325	6.11	2.5	0.9	1.3	4.3	51	0.3	0.7	0.4	125	3.19	0.088
1417586	Soil	1.2	39.6	20.2	78	<0.1	35.2	14.3	644	3.95	90.7	1.3	0.6	11.5	29	0.1	0.9	0.2	48	0.42	0.068
1417583	Soil	0.9	20.6	9.9	66	<0.1	15.8	8.5	351	3.07	12.2	0.7	1.5	4.4	22	<0.1	0.5	0.1	51	0.37	0.049
1417591	Soil	1.8	45.9	20.2	131	<0.1	37.2	15.2	830	4.08	11.5	0.9	1.3	9.7	22	0.1	0.5	0.2	76	0.48	0.098
1417600	Soil	1.7	39.0	28.8	101	0.2	35.3	13.4	734	3.14	27.8	1.6	0.8	5.4	50	0.5	0.7	0.2	57	0.64	0.083
1390376	Soil	1.9	53.2	35.3	117	0.3	60.0	16.9	765	3.57	84.6	1.5	3.3	3.8	54	0.8	0.9	0.3	56	0.76	0.087
1417599	Soil	1.9	46.5	27.0	110	0.2	38.9	12.3	711	3.10	25.1	1.9	1.4	4.8	63	0.5	0.7	0.2	57	0.89	0.092
1390383	Soil	2.7	83.8	50.1	221	0.2	59.4	19.5	1328	3.95	7.1	1.2	5.2	8.4	32	0.9	2.2	0.2	54	0.95	0.100
1418573	Soil	1.3	27.5	22.0	81	<0.1	27.5	12.0	347	3.65	26.2	1.1	<0.5	9.8	20	<0.1	0.7	0.2	44	0.18	0.042
1418572	Soil	1.3	28.8	14.2	73	<0.1	33.6	12.1	345	3.79	8.8	1.1	0.6	9.1	21	0.1	0.8	0.2	57	0.25	0.045
1418569	Soil	1.3	27.9	16.7	71	<0.1	40.5	14.4	390	3.74	28.6	1.2	1.6	10.5	21	<0.1	0.5	0.1	60	0.23	0.035
1418570	Soil	1.5	31.2	19.2	82	<0.1	42.7	13.8	629	4.21	38.8	1.3	3.5	9.1	15	0.1	0.5	0.2	65	0.14	0.076
1418571	Soil	0.9	25.5	13.0	63	<0.1	35.4	11.9	358	3.37	14.7	1.2	0.9	8.4	26	<0.1	0.5	0.1	59	0.31	0.042
1418565	Soil	1.1	16.5	10.5	65	<0.1	13.8	10.1	772	3.24	8.8	1.1	<0.5	4.2	40	<0.1	0.4	0.1	51	0.41	0.037
1418568	Soil	1.2	25.7	9.7	60	<0.1	20.1	13.4	388	3.71	22.6	1.0	1.0	5.4	21	<0.1	0.5	0.2	65	0.33	0.047
1418567	Soil	2.0	50.8	38.5	108	<0.1	44.4	15.6	722	4.40	48.4	1.3	<0.5	7.2	34	<0.1	2.2	0.3	56	0.29	0.069



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 8 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method Analyte Unit MDL	AQ201																	
	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te	
	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1390381	Soil	19	25	0.19	311	0.009	<1	0.88	0.008	0.10	<0.1	0.04	7.1	0.1	<0.05	3	<0.5	<0.2
1417593	Soil	16	42	0.49	519	0.044	1	1.23	0.019	0.19	0.1	0.06	10.7	0.1	<0.05	4	<0.5	<0.2
1390380	Soil	38	36	0.19	292	0.006	<1	0.91	0.006	0.21	<0.1	0.10	13.4	0.2	<0.05	3	<0.5	<0.2
1417595	Soil	16	90	0.91	761	0.036	1	1.43	0.012	0.47	<0.1	0.23	20.9	0.3	<0.05	5	0.6	<0.2
1417597	Soil	19	29	0.37	418	0.029	4	0.81	0.015	0.12	0.2	0.10	4.5	0.1	0.06	3	<0.5	<0.2
1417588	Soil	13	34	0.50	508	0.054	2	1.52	0.018	0.10	0.1	0.05	6.9	0.1	<0.05	5	<0.5	<0.2
1417598	Soil	20	33	0.50	476	0.050	2	1.15	0.018	0.10	0.2	0.06	5.3	<0.1	<0.05	4	<0.5	<0.2
1390377	Soil	15	14	0.18	1880	0.004	6	1.17	0.013	0.12	<0.1	0.34	8.0	0.2	0.10	2	<0.5	<0.2
1417584	Soil	14	34	0.49	324	0.072	1	1.43	0.014	0.23	0.2	0.06	7.3	0.2	<0.05	5	<0.5	<0.2
1417596	Soil	32	30	0.61	311	0.029	<1	1.03	0.012	0.33	<0.1	0.16	9.7	0.2	<0.05	4	<0.5	<0.2
1417589	Soil	18	69	0.67	492	0.035	1	1.46	0.028	0.30	<0.1	0.12	17.5	0.2	<0.05	5	<0.5	<0.2
1417585	Soil	15	17	0.38	430	0.021	2	1.14	0.006	0.35	<0.1	0.17	19.1	0.2	<0.05	4	<0.5	<0.2
1417592	Soil	25	93	0.94	817	0.129	1	1.91	0.010	0.65	0.1	0.12	15.9	0.4	<0.05	7	<0.5	<0.2
1390378	Soil	25	22	0.12	697	0.002	2	0.71	0.003	0.17	<0.1	0.25	13.5	0.2	<0.05	2	<0.5	<0.2
1390382	Soil	20	81	0.56	833	0.024	3	1.36	0.009	0.43	<0.1	0.10	25.5	0.2	<0.05	5	0.7	<0.2
1417586	Soil	27	32	0.39	333	0.043	2	1.09	0.010	0.28	0.1	0.08	8.9	0.2	<0.05	4	<0.5	<0.2
1417583	Soil	12	29	0.34	352	0.045	2	1.21	0.013	0.12	0.1	0.06	7.1	0.1	<0.05	4	<0.5	<0.2
1417591	Soil	17	52	0.77	500	0.115	3	1.73	0.012	0.60	<0.1	0.03	9.0	0.3	<0.05	6	<0.5	<0.2
1417600	Soil	18	34	0.40	564	0.024	3	1.03	0.011	0.12	0.1	0.18	8.7	0.1	<0.05	3	<0.5	<0.2
1390376	Soil	22	39	0.34	852	0.010	2	0.99	0.009	0.13	<0.1	0.20	11.0	0.1	<0.05	3	1.3	<0.2
1417599	Soil	18	32	0.42	710	0.021	3	0.99	0.011	0.12	0.1	0.19	9.7	0.2	0.05	3	1.0	<0.2
1390383	Soil	22	26	0.19	328	0.004	2	0.76	0.007	0.13	<0.1	0.42	9.9	0.2	<0.05	2	0.9	<0.2
1418573	Soil	22	31	0.37	289	0.038	2	1.49	0.007	0.29	<0.1	0.05	5.6	0.2	<0.05	5	<0.5	<0.2
1418572	Soil	30	48	0.75	345	0.073	1	1.93	0.009	0.36	0.1	0.03	5.4	0.3	<0.05	6	<0.5	<0.2
1418569	Soil	24	53	0.75	289	0.142	2	1.72	0.010	0.56	0.1	0.01	6.3	0.4	<0.05	6	<0.5	<0.2
1418570	Soil	28	57	0.87	251	0.112	2	2.30	0.012	0.57	0.1	0.04	6.1	0.4	<0.05	8	<0.5	<0.2
1418571	Soil	27	45	0.73	341	0.120	1	1.74	0.013	0.34	0.1	0.04	5.9	0.2	<0.05	6	<0.5	<0.2
1418565	Soil	14	21	0.38	618	0.022	2	1.40	0.012	0.11	0.1	0.06	9.4	0.1	<0.05	5	<0.5	<0.2
1418568	Soil	22	35	0.71	451	0.069	2	1.59	0.009	0.31	0.1	0.05	9.2	0.2	<0.05	5	<0.5	<0.2
1418567	Soil	15	27	0.15	495	0.002	3	0.89	0.004	0.09	<0.1	0.22	9.5	<0.1	<0.05	2	0.7	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 9 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%
		MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL
1418566	Soil	0.8	16.9	10.5	46	<0.1	15.1	8.2	373	2.57	9.2	0.9	4.4	3.6	27	0.1	0.4	<0.1	43	0.30	0.042
1418562	Soil	1.0	26.5	14.6	62	<0.1	26.9	11.5	377	3.02	11.7	1.0	3.1	6.8	30	<0.1	0.6	0.2	52	0.41	0.051
1418563	Soil	1.2	13.6	24.4	60	<0.1	20.0	11.0	485	2.81	24.9	0.5	<0.5	5.1	23	<0.1	0.6	0.2	44	0.27	0.051
1418564	Soil	0.7	17.2	8.2	54	<0.1	16.0	9.4	387	3.07	10.0	0.9	4.1	4.4	37	<0.1	0.4	0.1	55	0.45	0.043
1418560	Soil	0.9	29.4	14.7	63	<0.1	29.1	11.1	686	2.89	11.5	0.7	3.5	5.9	34	<0.1	0.6	0.2	50	0.54	0.050
1418561	Soil	1.2	21.0	14.4	53	<0.1	22.9	10.3	588	2.87	10.7	0.6	1.9	5.6	21	<0.1	0.5	0.2	52	0.23	0.032
1418557	Soil	0.8	31.1	12.1	52	<0.1	28.1	9.3	281	2.60	29.2	1.4	2.7	3.9	65	0.1	1.1	0.2	49	0.81	0.053
1418558	Soil	1.2	17.8	9.9	45	<0.1	23.3	9.3	273	2.56	13.8	0.7	1.6	3.8	26	<0.1	0.8	0.1	57	0.31	0.017
1418554	Soil	1.6	33.5	21.1	96	0.1	42.0	24.6	1173	4.18	8.8	1.0	2.7	4.7	55	0.2	0.2	0.2	123	0.62	0.118
1418556	Soil	0.6	39.3	10.2	59	<0.1	40.8	15.9	595	3.04	11.5	1.1	6.9	4.1	93	0.2	0.6	0.1	60	1.17	0.070
1418559	Soil	1.3	30.6	19.1	75	<0.1	30.5	12.5	425	3.68	23.1	1.0	1.2	9.2	32	<0.1	1.2	<0.1	50	0.35	0.035
1418553	Soil	1.4	53.1	14.2	91	0.1	54.9	23.9	831	5.41	7.7	1.1	2.9	7.7	84	0.1	0.3	0.2	161	0.90	0.123
1418555	Soil	1.0	27.1	15.3	44	0.1	28.1	12.7	605	2.65	18.0	1.3	<0.5	3.8	125	<0.1	0.9	0.2	35	1.37	0.053
1418552	Soil	2.1	55.0	18.7	110	<0.1	63.1	27.7	1056	5.78	15.8	1.4	3.9	7.2	72	0.2	0.5	0.2	107	0.86	0.121
1418551	Soil	1.3	25.3	12.2	65	<0.1	28.9	16.8	590	3.47	7.7	1.0	1.7	5.7	30	<0.1	0.4	0.1	60	0.33	0.042
1418586	Soil	1.9	39.8	17.9	65	<0.1	37.5	13.9	598	3.51	13.7	1.3	0.7	8.2	39	<0.1	1.0	0.2	50	0.27	0.049
1418585	Soil	0.6	62.9	10.7	76	<0.1	109.9	36.5	757	5.97	2.3	0.7	4.5	8.5	68	<0.1	0.2	0.1	253	1.00	0.168
1418584	Soil	1.4	41.2	13.2	78	<0.1	50.6	17.1	514	4.04	8.7	1.4	3.3	9.3	88	<0.1	0.7	0.1	58	0.65	0.183
1418583	Soil	1.1	31.6	12.1	73	<0.1	33.8	11.6	441	3.28	7.1	1.4	2.0	6.8	53	<0.1	0.6	0.2	56	0.56	0.102
1418582	Soil	1.2	35.1	12.9	71	<0.1	34.2	14.1	470	3.53	6.6	1.2	2.0	9.8	49	<0.1	0.5	0.2	49	0.47	0.093
1418581	Soil	1.0	44.2	12.5	64	<0.1	42.5	14.4	676	3.46	7.0	1.0	4.2	6.4	49	<0.1	0.6	0.2	69	0.66	0.090
1418580	Soil	1.0	32.5	17.9	64	<0.1	69.2	20.9	397	3.89	7.4	0.7	1.8	4.9	36	<0.1	0.5	0.2	90	0.45	0.056
1418579	Soil	1.5	23.1	11.6	56	<0.1	28.1	10.8	371	2.64	8.9	0.6	2.3	3.8	30	<0.1	0.6	0.2	57	0.42	0.039
1418578	Soil	1.1	36.2	11.8	71	<0.1	56.8	18.4	454	4.09	8.9	1.2	1.7	8.8	30	<0.1	0.6	0.1	62	0.48	0.082
1418577	Soil	1.2	10.2	7.6	43	<0.1	16.4	6.9	292	2.16	9.0	0.4	0.7	2.8	20	<0.1	0.3	0.1	55	0.24	0.057
1418575	Soil	0.9	20.8	13.3	55	<0.1	19.5	9.0	230	2.76	8.7	0.9	<0.5	7.0	17	<0.1	0.5	0.1	42	0.21	0.040
1418574	Soil	0.9	17.4	12.1	53	<0.1	21.5	10.0	240	2.80	9.2	1.0	0.8	7.5	18	<0.1	0.5	0.1	46	0.22	0.035
1418576	Soil	1.0	22.7	13.9	55	<0.1	23.2	9.5	240	2.77	11.8	0.8	3.9	6.8	21	<0.1	0.7	0.1	44	0.25	0.042



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 9 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
		ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL
1418566	Soil	14	21	0.35	353	0.033	2	1.29	0.012	0.11	0.1	0.06	5.8	<0.1	<0.05	4	<0.5	<0.2
1418562	Soil	23	33	0.38	540	0.044	2	1.46	0.010	0.14	0.1	0.06	6.6	0.1	<0.05	4	<0.5	<0.2
1418563	Soil	13	23	0.29	292	0.029	3	0.99	0.007	0.15	0.1	0.03	4.0	0.1	<0.05	3	<0.5	<0.2
1418564	Soil	15	25	0.52	465	0.050	3	1.47	0.015	0.22	0.1	0.04	9.2	0.1	<0.05	5	<0.5	<0.2
1418560	Soil	17	29	0.45	344	0.053	2	1.29	0.018	0.14	0.1	0.08	6.4	0.1	<0.05	4	<0.5	<0.2
1418561	Soil	13	29	0.32	324	0.049	1	1.34	0.012	0.13	0.1	0.03	4.8	0.1	<0.05	4	<0.5	<0.2
1418557	Soil	16	30	0.46	449	0.044	2	1.32	0.017	0.10	0.1	0.23	5.8	<0.1	<0.05	4	<0.5	<0.2
1418558	Soil	12	34	0.42	417	0.055	2	1.50	0.011	0.07	0.1	0.02	5.0	<0.1	<0.05	4	<0.5	<0.2
1418554	Soil	26	69	1.04	436	0.093	3	1.79	0.015	0.42	0.1	0.16	9.3	0.3	<0.05	6	<0.5	<0.2
1418556	Soil	20	37	0.51	456	0.044	3	1.28	0.017	0.17	0.1	0.12	8.6	0.1	<0.05	4	<0.5	<0.2
1418559	Soil	18	31	0.33	394	0.038	2	1.27	0.012	0.14	0.1	0.06	6.5	0.1	<0.05	4	<0.5	<0.2
1418553	Soil	40	85	1.37	513	0.119	3	2.10	0.013	0.62	<0.1	0.10	17.1	0.4	<0.05	7	<0.5	<0.2
1418555	Soil	15	22	0.43	292	0.018	3	0.81	0.014	0.13	<0.1	0.27	5.8	0.1	0.05	2	<0.5	<0.2
1418552	Soil	34	56	0.54	634	0.028	2	1.35	0.009	0.31	<0.1	0.09	16.6	0.2	<0.05	4	<0.5	<0.2
1418551	Soil	21	33	0.41	375	0.050	2	1.53	0.010	0.16	<0.1	0.04	6.0	0.2	<0.05	5	<0.5	<0.2
1418586	Soil	27	30	0.31	419	0.019	<1	1.23	0.009	0.14	<0.1	0.04	6.6	0.1	<0.05	4	<0.5	<0.2
1418585	Soil	33	258	3.50	755	0.229	1	3.60	0.015	1.37	<0.1	0.03	10.3	0.6	<0.05	12	<0.5	<0.2
1418584	Soil	39	52	0.63	475	0.067	1	1.64	0.012	0.27	<0.1	0.09	8.5	0.2	<0.05	5	<0.5	<0.2
1418583	Soil	29	38	0.54	534	0.063	<1	1.53	0.012	0.21	0.1	0.09	7.3	0.1	<0.05	5	<0.5	<0.2
1418582	Soil	29	34	0.43	390	0.056	2	1.15	0.014	0.21	0.2	0.05	6.3	0.2	<0.05	4	<0.5	<0.2
1418581	Soil	26	47	0.63	439	0.065	2	1.42	0.020	0.19	0.2	0.06	8.2	0.2	<0.05	5	<0.5	<0.2
1418580	Soil	17	90	0.90	345	0.075	2	1.68	0.012	0.18	<0.1	0.04	7.6	0.2	<0.05	6	<0.5	<0.2
1418579	Soil	13	34	0.38	326	0.048	3	1.33	0.010	0.11	<0.1	0.05	4.2	0.1	<0.05	4	<0.5	<0.2
1418578	Soil	23	63	0.57	374	0.037	2	1.54	0.009	0.18	<0.1	0.07	8.4	0.1	<0.05	5	<0.5	<0.2
1418577	Soil	12	28	0.36	186	0.066	2	0.95	0.008	0.12	0.1	0.02	2.6	<0.1	<0.05	5	0.6	<0.2
1418575	Soil	16	24	0.32	243	0.027	1	1.30	0.008	0.13	0.1	0.03	4.1	0.1	<0.05	4	<0.5	<0.2
1418574	Soil	19	29	0.40	353	0.043	2	1.37	0.008	0.13	<0.1	0.02	4.4	0.1	<0.05	4	<0.5	<0.2
1418576	Soil	17	26	0.36	286	0.030	2	1.18	0.008	0.09	<0.1	0.03	4.1	<0.1	<0.05	3	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000144.1

Method	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
Analyte	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
Pulp Duplicates																					
1390390	Soil	2.6	44.4	40.5	148	<0.1	33.1	12.1	484	3.98	15.7	1.5	0.7	9.0	20	0.3	0.6	0.3	66	0.17	0.069
REP 1390390	QC	2.6	42.2	39.5	140	<0.1	30.9	11.6	462	3.92	15.4	1.5	2.5	9.0	17	0.3	0.5	0.2	66	0.17	0.064
1352835	Soil	1.1	16.2	8.5	80	<0.1	20.2	12.6	473	4.27	6.4	0.7	<0.5	5.6	21	<0.1	0.3	<0.1	72	0.34	0.048
REP 1352835	QC	1.1	16.1	8.5	80	<0.1	19.8	12.7	489	4.64	6.3	0.7	<0.5	5.7	20	<0.1	0.3	<0.1	75	0.34	0.049
1392844	Soil	0.8	34.3	11.9	69	0.1	36.0	12.4	427	3.01	9.0	1.3	3.5	6.0	63	0.2	0.7	0.1	51	0.78	0.101
REP 1392844	QC	0.8	36.3	11.5	71	0.1	36.6	12.9	450	3.15	8.8	1.3	4.8	5.8	61	0.1	0.6	0.1	51	0.77	0.099
1390441	Soil	1.6	42.1	35.7	119	<0.1	36.5	11.9	335	3.85	41.2	1.4	2.4	8.6	19	0.1	1.9	0.4	59	0.18	0.045
REP 1390441	QC	1.4	39.7	35.8	114	<0.1	36.4	12.4	322	3.87	39.8	1.4	0.5	8.7	19	0.2	1.9	0.4	56	0.18	0.044
1335741	Soil	0.7	32.8	15.1	51	0.1	26.2	9.6	336	2.50	12.2	0.5	5.1	4.4	27	<0.1	0.8	0.1	52	0.41	0.043
REP 1335741	QC	0.7	35.0	15.8	54	0.1	27.6	9.7	347	2.69	12.9	0.5	5.3	4.6	27	<0.1	0.7	0.2	55	0.43	0.041
1417597	Soil	1.1	32.0	18.6	55	<0.1	32.4	12.5	601	2.68	10.0	1.5	2.7	2.9	106	0.1	0.8	0.1	40	1.31	0.091
REP 1417597	QC	1.3	34.7	19.4	58	<0.1	34.1	12.7	624	2.81	10.0	1.6	7.3	2.9	111	0.1	0.8	0.2	42	1.34	0.094
1418556	Soil	0.6	39.3	10.2	59	<0.1	40.8	15.9	595	3.04	11.5	1.1	6.9	4.1	93	0.2	0.6	0.1	60	1.17	0.070
REP 1418556	QC	0.8	39.5	9.9	58	<0.1	40.5	15.7	585	3.03	10.9	1.1	4.0	3.9	88	<0.1	0.6	0.1	58	1.10	0.065
1418576	Soil	1.0	22.7	13.9	55	<0.1	23.2	9.5	240	2.77	11.8	0.8	3.9	6.8	21	<0.1	0.7	0.1	44	0.25	0.042
REP 1418576	QC	0.9	22.3	13.6	53	<0.1	22.8	9.3	236	2.74	11.2	0.8	2.7	7.0	20	<0.1	0.8	0.1	43	0.25	0.041
Reference Materials																					
STD DS10	Standard	15.0	150.5	148.7	364	1.8	73.4	12.5	873	2.75	45.6	2.7	68.0	7.7	71	2.4	9.9	12.3	44	1.07	0.073
STD DS10	Standard	14.6	156.9	152.2	373	1.8	75.8	13.2	925	2.87	46.0	2.7	82.7	7.8	72	2.6	10.1	12.7	44	1.06	0.074
STD DS10	Standard	15.3	152.1	145.1	364	1.9	74.5	13.0	881	2.72	47.0	2.6	73.3	7.4	63	2.8	9.3	11.4	42	1.10	0.072
STD DS10	Standard	14.7	158.6	150.4	365	2.0	75.0	13.3	914	2.77	46.1	2.6	74.3	7.3	65	2.5	9.7	11.4	43	1.01	0.075
STD DS10	Standard	14.9	140.1	146.2	369	1.9	72.2	12.1	891	2.76	45.7	2.6	75.3	7.4	65	2.9	9.1	11.9	42	1.03	0.071
STD DS10	Standard	14.1	143.0	141.4	367	1.8	74.7	12.9	871	2.80	43.5	2.6	70.3	7.4	62	2.6	9.3	10.9	42	1.02	0.070
STD DS10	Standard	14.2	158.1	150.1	367	1.9	74.5	12.5	908	2.77	46.2	2.7	68.3	7.8	73	2.6	10.0	12.6	45	1.08	0.079
STD DS10	Standard	14.1	153.9	147.7	366	1.8	72.6	12.9	877	2.71	43.8	2.6	99.2	7.7	71	2.4	10.1	12.4	44	1.03	0.076
STD OXC129	Standard	1.1	26.4	6.6	41	<0.1	78.3	20.0	427	3.03	<0.5	0.7	197.0	2.0	196	<0.1	<0.1	<0.1	52	0.69	0.102
STD OXC129	Standard	1.2	26.7	6.4	39	<0.1	77.1	19.4	420	2.96	<0.5	0.7	194.8	1.8	186	<0.1	<0.1	<0.1	51	0.66	0.101
STD OXC129	Standard	1.4	27.2	6.3	41	<0.1	77.0	20.5	408	3.13	0.7	0.6	195.0	1.7	186	<0.1	<0.1	<0.1	54	0.69	0.099



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000144.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																		
1390390	Soil	17	33	0.25	265	0.029	<1	1.31	0.007	0.13	<0.1	0.06	6.3	0.1	<0.05	4	<0.5	<0.2
REP 1390390	QC	18	32	0.25	261	0.029	<1	1.25	0.008	0.13	0.1	0.06	5.9	0.1	<0.05	5	0.8	<0.2
1352835	Soil	11	59	1.39	328	0.187	1	2.48	0.010	0.86	0.2	0.01	9.8	0.4	<0.05	11	0.7	<0.2
REP 1352835	QC	11	59	1.45	327	0.180	<1	2.58	0.011	0.76	0.1	<0.01	9.7	0.3	<0.05	11	<0.5	<0.2
1392844	Soil	26	39	0.58	528	0.062	2	1.42	0.021	0.17	0.2	0.09	7.1	0.1	<0.05	5	1.1	<0.2
REP 1392844	QC	26	39	0.56	515	0.062	3	1.39	0.020	0.18	0.2	0.09	7.0	0.1	<0.05	4	0.8	<0.2
1390441	Soil	18	31	0.32	280	0.030	<1	1.24	0.010	0.22	0.1	0.01	5.8	0.2	<0.05	5	0.8	<0.2
REP 1390441	QC	18	29	0.31	285	0.030	1	1.25	0.009	0.21	<0.1	0.02	5.7	0.2	<0.05	4	1.0	<0.2
1335741	Soil	16	29	0.47	280	0.065	1	1.12	0.019	0.08	0.1	0.05	5.4	<0.1	<0.05	3	<0.5	<0.2
REP 1335741	QC	16	29	0.46	277	0.067	<1	1.15	0.021	0.09	0.2	0.06	5.6	<0.1	<0.05	3	<0.5	<0.2
1417597	Soil	19	29	0.37	418	0.029	4	0.81	0.015	0.12	0.2	0.10	4.5	0.1	0.06	3	<0.5	<0.2
REP 1417597	QC	19	30	0.36	432	0.029	4	0.84	0.015	0.13	0.2	0.10	4.5	0.1	0.05	3	<0.5	<0.2
1418556	Soil	20	37	0.51	456	0.044	3	1.28	0.017	0.17	0.1	0.12	8.6	0.1	<0.05	4	<0.5	<0.2
REP 1418556	QC	20	35	0.50	443	0.041	2	1.21	0.016	0.16	0.1	0.12	7.9	0.1	<0.05	4	<0.5	<0.2
1418576	Soil	17	26	0.36	286	0.030	2	1.18	0.008	0.09	<0.1	0.03	4.1	<0.1	<0.05	3	<0.5	<0.2
REP 1418576	QC	17	25	0.35	281	0.029	1	1.18	0.008	0.09	0.1	0.03	4.2	<0.1	<0.05	3	0.6	<0.2
Reference Materials																		
STD DS10	Standard	18	55	0.76	374	0.083	7	1.05	0.068	0.34	3.4	0.29	3.1	5.2	0.26	4	2.0	5.0
STD DS10	Standard	18	55	0.81	349	0.082	8	1.07	0.071	0.34	3.5	0.28	2.9	5.4	0.29	4	2.1	5.1
STD DS10	Standard	18	54	0.77	375	0.079	9	1.05	0.064	0.37	3.5	0.31	3.4	5.1	0.24	5	2.6	4.9
STD DS10	Standard	17	56	0.80	358	0.075	6	1.04	0.065	0.32	3.4	0.27	3.2	5.3	0.23	5	2.8	5.0
STD DS10	Standard	18	55	0.81	350	0.076	5	1.09	0.066	0.31	3.2	0.28	3.1	5.1	0.30	5	2.8	5.0
STD DS10	Standard	18	54	0.74	362	0.073	7	0.99	0.062	0.32	3.2	0.28	2.8	5.0	0.24	5	2.8	4.6
STD DS10	Standard	18	56	0.78	362	0.084	8	1.07	0.076	0.34	3.1	0.30	3.1	5.0	0.30	4	2.2	4.8
STD DS10	Standard	18	56	0.76	362	0.082	8	1.07	0.069	0.33	3.2	0.29	3.1	4.9	0.28	4	2.1	4.4
STD OXC129	Standard	13	52	1.53	51	0.406	2	1.57	0.572	0.35	<0.1	<0.01	1.0	<0.1	<0.05	6	<0.5	<0.2
STD OXC129	Standard	13	49	1.54	49	0.400	<1	1.50	0.585	0.36	<0.1	<0.01	0.6	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	12	54	1.57	49	0.371	<1	1.65	0.616	0.38	0.1	<0.01	1.5	<0.1	<0.05	6	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 09, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT WHI16000144.1

		AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%
		0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001
STD OXC129	Standard	1.3	26.6	6.4	40	<0.1	78.6	19.6	441	3.04	<0.5	0.6	202.9	1.7	175	<0.1	<0.1	<0.1	49	0.60	0.109
STD OXC129	Standard	1.3	26.2	6.3	41	<0.1	80.4	20.3	396	3.05	0.7	0.7	199.2	1.8	185	<0.1	<0.1	<0.1	53	0.71	0.103
STD OXC129	Standard	1.2	26.6	6.2	40	<0.1	79.5	20.2	416	3.19	0.7	0.7	191.8	1.9	185	<0.1	<0.1	<0.1	54	0.76	0.094
STD OXC129	Standard	1.4	27.9	6.4	41	<0.1	80.0	20.6	427	3.07	<0.5	0.7	199.7	1.8	188	<0.1	<0.1	<0.1	55	0.66	0.108
STD OXC129	Standard	1.2	27.1	6.4	41	<0.1	78.5	19.8	424	3.05	<0.5	0.7	191.1	1.8	186	<0.1	<0.1	<0.1	53	0.66	0.104
STD DS10 Expected		15.1	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	2.59	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	0.0765
STD OXC129 Expected		1.3	28	6.3	42.9		79.5	20.3	421	3.065	0.6	0.72	195	1.9					51	0.665	0.102
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



QUALITY CONTROL REPORT

WHI16000144.1

		AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD OXC129	Standard	12	47	1.59	49	0.352	<1	1.56	0.599	0.38	<0.1	<0.01	1.5	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	12	51	1.54	51	0.370	1	1.59	0.604	0.35	<0.1	0.01	1.3	<0.1	<0.05	6	<0.5	<0.2
STD OXC129	Standard	11	51	1.55	50	0.386	2	1.51	0.559	0.36	0.1	<0.01	1.0	<0.1	<0.05	6	<0.5	<0.2
STD OXC129	Standard	13	53	1.56	51	0.409	1	1.57	0.600	0.38	<0.1	<0.01	0.9	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	13	51	1.53	49	0.400	2	1.54	0.608	0.37	<0.1	<0.01	0.7	<0.1	<0.05	5	<0.5	<0.2
STD DS10 Expected		17.5	54.6	0.775	359	0.0817		1.0755	0.067	0.338	3.32	0.3	3	5.1	0.29	4.5	2.3	5.01
STD OXC129 Expected		13	52	1.545	50	0.4	1	1.58	0.6	0.37			1.1			5.6		
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 23, 2016
Report Date: September 09, 2016
Page: 1 of 9

CERTIFICATE OF ANALYSIS

WHI16000209.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV2016-08-19Soil
P.O. Number
Number of Samples: 213

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT-SOIL Immediate Disposal of Soil Reject

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Dry at 60C	213	Dry at 60C			WHI
SS80	213	Dry at 60C sieve 100g to -80 mesh			WHI
AQ201	213	1:1:1 Aqua Regia digestion ICP-MS analysis	15	Completed	VAN
SHP01	213	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 2 of 9 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
Unit		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL		0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	2	0.01	0.001	
1390489	Soil	1.5	21.5	24.3	72	0.1	17.1	9.1	609	3.36	13.3	1.8	15.0	23.2	21	0.2	0.5	0.3	44	0.39	0.052
1390491	Soil	0.8	30.6	8.4	71	<0.1	26.0	10.5	430	2.60	10.3	0.9	6.1	4.1	39	0.2	0.7	0.2	52	0.75	0.077
1390493	Soil	0.8	34.1	9.0	71	0.1	24.3	9.2	337	2.55	9.0	1.0	4.1	4.2	48	0.3	0.7	0.2	52	0.96	0.094
1390492	Soil	0.6	21.2	7.2	70	<0.1	19.6	8.7	335	2.23	6.4	1.1	6.3	4.8	44	0.3	0.4	0.2	45	0.89	0.097
1390497	Soil	1.0	27.0	19.0	56	0.1	21.1	9.1	448	2.93	14.7	1.1	21.7	13.3	23	<0.1	0.5	0.2	50	0.40	0.055
1390495	Soil	0.6	10.3	26.2	64	0.2	7.1	6.0	574	3.49	16.7	1.3	22.6	20.2	17	0.1	0.4	0.9	51	0.56	0.057
1390494	Soil	3.0	15.7	33.0	97	0.2	10.2	10.4	803	3.80	14.5	1.7	55.8	22.0	33	0.3	0.4	0.6	46	0.76	0.123
1390496	Soil	1.3	16.1	10.8	58	0.1	19.2	10.2	483	2.91	9.5	0.7	2.9	9.0	24	<0.1	0.5	0.2	52	0.43	0.053
1390499	Soil	1.4	23.0	20.4	66	0.1	27.7	10.9	447	2.90	10.3	0.7	4.8	8.5	30	<0.1	0.7	0.2	57	0.46	0.045
1390500	Soil	0.6	28.3	18.4	94	<0.1	20.8	12.4	766	3.93	6.7	0.8	3.2	14.6	32	<0.1	0.5	0.2	59	0.68	0.083
1390498	Soil	0.6	32.4	17.5	105	<0.1	18.8	13.1	883	4.46	10.4	1.1	8.0	19.6	25	<0.1	0.5	0.2	60	0.52	0.088
1390476	Soil	1.1	26.0	16.5	63	<0.1	22.1	9.9	344	2.74	8.9	2.1	7.3	7.6	40	0.2	0.5	0.2	57	0.56	0.073
1390478	Soil	0.9	33.0	10.9	66	0.1	26.9	10.7	463	2.70	8.8	1.0	3.5	4.9	45	0.3	0.6	0.2	55	0.90	0.075
1390477	Soil	1.2	27.3	14.4	66	0.1	24.0	9.6	463	2.81	7.6	1.1	1.1	5.7	38	0.2	0.6	0.2	56	0.63	0.075
1390479	Soil	1.1	35.0	9.5	74	0.1	28.1	10.6	492	2.65	10.5	0.9	3.3	4.3	64	0.5	0.9	0.1	55	2.07	0.087
1390481	Soil	0.7	27.4	8.7	83	0.1	25.9	9.1	425	2.26	8.6	0.6	3.9	3.7	45	0.5	0.8	0.1	39	1.47	0.079
1390480	Soil	1.0	32.2	10.8	66	0.1	27.3	11.2	495	2.47	9.8	1.9	3.6	4.8	53	0.3	0.8	0.1	52	0.87	0.074
1390483	Soil	1.1	26.4	10.1	87	<0.1	16.4	14.0	797	3.74	5.7	1.0	2.6	13.4	29	<0.1	0.4	<0.1	59	0.55	0.120
1390488	Soil	3.0	16.4	22.3	55	0.2	17.2	9.7	602	2.79	36.8	1.3	24.8	10.1	29	0.1	0.6	0.3	45	0.31	0.052
1390482	Soil	0.9	27.1	13.6	70	<0.1	22.4	11.0	607	2.89	10.0	0.7	4.9	6.1	32	0.2	0.7	0.2	56	0.57	0.053
1390484	Soil	0.9	19.0	12.4	111	<0.1	18.1	16.7	1002	4.96	6.6	1.3	2.3	19.9	23	<0.1	0.4	<0.1	74	0.37	0.065
1390486	Soil	0.9	25.3	40.1	76	0.1	21.8	11.8	682	3.63	7.7	1.0	3.6	12.2	26	0.2	0.5	0.7	60	0.40	0.055
1390485	Soil	1.7	25.2	16.9	94	<0.1	22.4	11.8	677	4.07	11.8	1.3	9.0	14.8	24	0.2	0.5	0.1	65	0.36	0.074
1390487	Soil	1.4	34.0	88.3	107	<0.1	23.6	14.1	708	4.58	9.3	1.7	1.3	22.2	34	0.1	0.6	0.9	69	0.49	0.071
1418663	Soil	0.5	25.2	17.3	90	<0.1	19.3	11.7	595	3.92	10.6	1.4	7.9	22.2	25	<0.1	0.5	0.2	55	0.45	0.092
1418662	Soil	0.2	20.8	28.4	85	0.1	8.6	10.9	817	4.27	37.0	2.4	41.9	23.7	23	<0.1	0.3	0.2	31	0.45	0.090
1418664	Soil	0.5	14.0	21.5	68	<0.1	7.3	8.3	656	3.21	6.3	1.1	6.1	12.2	16	0.1	0.2	0.3	46	0.41	0.113
1418661	Soil	0.5	20.2	8.9	105	<0.1	17.7	12.6	778	4.45	6.5	1.9	5.3	22.1	20	<0.1	0.3	0.2	63	0.46	0.101
1418660	Soil	0.6	19.2	13.3	116	<0.1	9.8	14.2	1030	4.94	2.6	1.9	11.6	36.5	18	<0.1	0.2	0.2	62	0.59	0.161
1418659	Soil	3.6	21.7	19.0	131	0.1	11.1	14.6	1096	5.19	8.2	3.9	26.3	28.7	25	0.2	0.3	0.3	67	0.66	0.096



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 2 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte Unit MDL	AQ201																	
	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te	
	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
	1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1390489	Soil	54	22	0.37	206	0.031	1	1.49	0.008	0.28	0.3	0.03	6.8	0.2	<0.05	5	<0.5	<0.2
1390491	Soil	16	29	0.59	318	0.078	2	1.34	0.033	0.06	0.2	0.04	4.8	<0.1	<0.05	4	<0.5	<0.2
1390493	Soil	17	27	0.59	312	0.079	3	1.24	0.033	0.10	0.3	0.03	4.5	<0.1	<0.05	4	0.6	<0.2
1390492	Soil	16	25	0.53	272	0.076	3	1.10	0.027	0.10	0.3	0.02	3.8	<0.1	<0.05	4	<0.5	<0.2
1390497	Soil	29	26	0.48	240	0.061	<1	1.44	0.014	0.28	0.4	<0.01	6.2	0.2	<0.05	5	<0.5	<0.2
1390495	Soil	45	10	0.19	138	0.004	2	1.32	0.005	0.30	0.3	<0.01	6.5	0.1	<0.05	5	<0.5	<0.2
1390494	Soil	62	14	0.34	260	0.017	2	1.40	0.010	0.33	0.3	0.03	8.6	0.1	<0.05	6	<0.5	<0.2
1390496	Soil	21	31	0.42	255	0.063	1	1.73	0.010	0.22	0.2	<0.01	6.1	0.1	<0.05	5	<0.5	<0.2
1390499	Soil	27	39	0.52	275	0.104	2	1.69	0.017	0.26	0.2	0.01	7.1	0.1	<0.05	6	<0.5	<0.2
1390500	Soil	44	23	0.93	269	0.112	2	2.01	0.018	0.56	0.2	0.03	7.2	0.3	<0.05	9	<0.5	<0.2
1390498	Soil	66	22	1.04	300	0.150	<1	2.35	0.013	0.97	0.2	0.02	7.9	0.5	<0.05	10	<0.5	<0.2
1390476	Soil	27	36	0.53	247	0.107	1	1.64	0.023	0.08	0.3	<0.01	6.6	0.1	<0.05	6	<0.5	<0.2
1390478	Soil	21	29	0.60	362	0.081	2	1.46	0.030	0.07	0.2	0.03	4.8	<0.1	<0.05	5	<0.5	<0.2
1390477	Soil	22	32	0.58	315	0.078	2	1.68	0.025	0.07	0.2	0.04	5.5	<0.1	<0.05	6	<0.5	<0.2
1390479	Soil	16	28	0.78	396	0.086	2	1.25	0.038	0.09	0.2	0.02	4.5	<0.1	<0.05	4	<0.5	<0.2
1390481	Soil	14	23	0.71	394	0.054	2	1.04	0.022	0.05	0.2	0.03	3.4	<0.1	<0.05	3	0.6	<0.2
1390480	Soil	21	32	0.52	388	0.087	2	1.45	0.028	0.07	0.3	0.03	4.9	<0.1	<0.05	5	<0.5	<0.2
1390483	Soil	40	24	0.69	362	0.091	1	2.15	0.011	0.45	0.1	0.02	6.8	0.2	<0.05	9	<0.5	<0.2
1390488	Soil	29	25	0.35	246	0.045	<1	1.36	0.011	0.23	0.2	<0.01	5.6	0.1	<0.05	4	<0.5	0.2
1390482	Soil	20	31	0.53	303	0.085	<1	1.76	0.022	0.13	0.2	0.03	5.7	0.1	<0.05	6	<0.5	<0.2
1390484	Soil	27	28	1.18	321	0.188	<1	2.65	0.010	0.94	0.1	<0.01	7.2	0.4	<0.05	12	<0.5	<0.2
1390486	Soil	39	29	0.79	234	0.111	1	2.14	0.010	0.53	0.2	0.01	6.8	0.2	<0.05	8	<0.5	<0.2
1390485	Soil	35	34	0.80	258	0.144	2	2.29	0.011	0.59	0.1	<0.01	9.6	0.3	<0.05	9	<0.5	<0.2
1390487	Soil	44	30	1.02	253	0.150	2	2.56	0.009	0.55	0.3	<0.01	8.0	0.3	<0.05	12	<0.5	<0.2
1418663	Soil	58	27	0.72	322	0.076	<1	2.11	0.015	0.55	0.1	<0.01	8.0	0.2	<0.05	8	<0.5	<0.2
1418662	Soil	59	9	0.46	278	0.003	<1	1.75	0.007	0.26	0.4	0.06	5.8	0.1	<0.05	5	<0.5	<0.2
1418664	Soil	17	13	0.61	235	0.103	<1	1.62	0.009	0.29	0.2	<0.01	4.2	0.1	<0.05	8	<0.5	<0.2
1418661	Soil	59	25	0.95	312	0.136	<1	2.22	0.013	0.63	0.1	0.01	8.0	0.3	<0.05	11	<0.5	<0.2
1418660	Soil	91	15	1.22	271	0.176	1	2.56	0.008	1.22	<0.1	<0.01	6.8	0.5	<0.05	12	<0.5	<0.2
1418659	Soil	67	15	0.97	379	0.116	<1	2.37	0.010	0.71	0.2	0.02	10.0	0.4	<0.05	11	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 3 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte Unit MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppb	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	
	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1418658	Soil	0.8	30.4	14.3	70	0.1	21.9	10.4	482	2.76	7.9	1.4	3.2	6.0	44	0.3	0.4	0.3	52	0.86	0.054
1418665	Soil	0.3	9.3	7.4	76	<0.1	5.8	7.9	706	3.50	4.3	1.1	1.0	10.0	18	<0.1	0.1	<0.1	50	0.40	0.135
1418656	Soil	0.9	35.9	18.1	133	0.1	25.8	16.4	1180	4.89	11.6	2.1	18.7	23.4	32	0.3	0.4	0.8	68	0.58	0.086
1418657	Soil	0.5	40.3	8.4	63	0.1	23.4	8.6	449	2.29	6.3	1.4	2.4	4.2	54	0.5	0.5	0.3	44	1.02	0.070
1418654	Soil	0.8	28.1	8.9	62	<0.1	24.6	9.8	484	2.67	8.5	1.1	5.6	6.7	37	0.1	0.5	0.4	54	0.64	0.084
1418655	Soil	0.5	37.0	9.1	55	0.1	23.0	9.5	539	2.53	7.9	1.1	3.6	4.9	44	0.1	0.4	0.6	49	0.80	0.076
1418653	Soil	0.9	31.6	28.9	82	0.1	21.6	11.7	433	2.96	8.4	3.4	8.6	8.5	40	0.2	0.5	0.6	54	0.69	0.090
1418650	Soil	2.0	43.4	10.1	124	0.1	21.9	14.5	722	4.15	6.8	1.9	4.6	18.8	33	0.4	0.4	0.4	64	0.70	0.119
1418649	Soil	1.8	48.0	10.8	133	0.1	20.8	16.7	822	4.71	7.1	2.1	16.1	21.3	32	0.4	0.3	0.3	69	0.74	0.141
1418651	Soil	0.9	39.8	11.0	87	0.1	29.5	12.4	479	2.97	10.3	0.8	3.7	4.6	50	0.4	0.7	0.3	58	1.13	0.086
1418652	Soil	1.0	45.2	11.2	82	0.1	25.4	9.9	485	2.77	6.6	1.7	5.2	7.1	45	0.4	0.6	0.3	53	0.87	0.082
1418720	Soil	1.5	63.2	74.0	146	<0.1	14.0	14.4	987	4.78	4.6	1.8	1.3	33.9	18	0.1	0.2	1.0	66	0.47	0.138
1418713	Soil	0.7	12.1	6.5	103	<0.1	8.0	11.4	883	4.06	2.0	1.3	5.4	20.4	22	<0.1	0.3	<0.1	47	1.10	0.073
1418721	Soil	1.5	19.3	10.6	94	<0.1	12.0	11.2	637	4.06	5.0	1.5	1.2	21.4	17	<0.1	0.4	0.3	57	0.31	0.090
1418714	Soil	1.7	31.5	12.7	80	0.1	18.9	10.9	563	2.63	9.7	1.3	20.2	5.1	36	0.5	0.5	1.9	52	0.72	0.084
1418715	Soil	1.9	308.8	15.3	176	<0.1	9.0	14.2	811	4.60	3.8	1.6	1.6	29.5	20	0.2	0.2	4.9	54	0.47	0.137
1418722	Soil	2.1	6.3	6.2	63	<0.1	7.0	9.4	777	2.87	3.7	0.9	1.9	13.0	9	<0.1	0.2	0.1	39	0.24	0.083
1418709	Soil	1.5	24.8	15.5	60	<0.1	18.1	8.9	559	2.99	6.4	1.6	5.3	11.3	24	<0.1	0.3	0.2	46	0.34	0.049
1418712	Soil	1.9	9.5	23.3	56	<0.1	12.5	6.7	1330	2.32	6.1	1.0	8.3	6.2	25	0.3	0.3	0.2	40	0.35	0.058
1418711	Soil	1.0	17.0	6.9	112	<0.1	11.0	14.6	1028	4.50	2.3	2.5	<0.5	21.0	27	<0.1	0.1	<0.1	54	0.52	0.113
1418718	Soil	2.1	221.7	55.7	194	0.2	8.6	15.7	394	4.52	79.7	7.3	8.9	15.8	49	0.3	0.4	2.4	24	0.22	0.039
1418716	Soil	1.1	45.3	11.5	151	<0.1	11.5	15.6	1253	5.23	2.9	1.8	2.8	24.7	32	0.3	0.3	0.7	82	0.79	0.190
1418719	Soil	2.8	158.9	22.6	183	0.2	13.3	13.1	798	5.08	17.0	3.9	13.5	15.2	17	0.3	0.3	1.7	58	0.27	0.068
1368494	Soil	1.0	32.4	10.3	78	0.1	25.2	10.7	489	2.75	9.2	1.1	3.8	7.0	40	0.3	0.7	0.2	52	0.78	0.093
1368497	Soil	1.5	17.5	13.6	86	<0.1	11.4	9.9	389	3.92	6.6	1.6	2.1	19.8	24	<0.1	0.3	0.2	56	0.45	0.060
1368498	Soil	0.7	31.2	12.6	109	<0.1	22.8	13.1	840	4.35	7.3	1.3	5.0	18.5	31	<0.1	0.4	0.1	65	0.56	0.081
1418710	Soil	1.2	21.5	28.3	90	<0.1	10.7	7.7	521	3.52	7.8	1.4	0.9	5.6	17	0.1	0.4	0.3	53	0.21	0.031
1368492	Soil	0.7	30.0	7.7	63	<0.1	25.1	10.1	434	2.36	9.3	0.7	3.6	3.7	70	0.4	0.7	0.1	50	2.15	0.083
1368495	Soil	0.5	27.7	9.3	59	<0.1	18.7	8.6	391	2.54	7.2	1.2	3.0	4.8	53	<0.1	0.3	0.3	47	1.10	0.091
1368496	Soil	0.6	36.9	22.2	58	0.3	18.9	8.8	526	2.22	7.6	1.4	14.8	6.6	165	0.4	0.8	0.2	39	11.89	0.093



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 3 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.1	0.01	0.05	1	0.5	0.2	
1418658	Soil	22	28	0.59	297	0.083	1	1.49	0.026	0.20	0.2	0.02	5.0	0.1	<0.05	5	<0.5	<0.2
1418665	Soil	16	11	0.79	172	0.164	<1	1.92	0.008	0.50	0.2	<0.01	5.9	0.2	<0.05	9	<0.5	<0.2
1418656	Soil	56	29	1.15	402	0.130	<1	2.40	0.022	0.86	0.2	0.04	8.6	0.4	<0.05	11	<0.5	<0.2
1418657	Soil	22	25	0.54	308	0.078	2	1.33	0.028	0.16	0.2	0.02	4.5	0.1	<0.05	4	<0.5	<0.2
1418654	Soil	20	29	0.64	190	0.094	1	1.30	0.035	0.17	0.2	0.01	4.3	0.1	<0.05	5	<0.5	<0.2
1418655	Soil	22	26	0.57	356	0.084	1	1.33	0.033	0.11	0.2	0.03	4.4	<0.1	<0.05	5	0.6	<0.2
1418653	Soil	24	27	0.65	241	0.097	2	1.33	0.028	0.22	0.2	0.03	4.4	0.1	<0.05	5	0.7	<0.2
1418650	Soil	51	32	0.87	318	0.111	2	1.89	0.021	0.45	0.2	0.03	8.3	0.3	<0.05	8	<0.5	<0.2
1418649	Soil	54	30	0.98	302	0.114	2	1.98	0.019	0.53	0.2	0.04	9.0	0.3	<0.05	9	0.5	<0.2
1418651	Soil	18	32	0.84	299	0.091	3	1.47	0.038	0.14	0.2	0.02	5.1	0.1	<0.05	5	<0.5	<0.2
1418652	Soil	30	28	0.68	321	0.090	3	1.44	0.030	0.21	0.2	0.04	5.0	0.1	<0.05	5	<0.5	<0.2
1418720	Soil	47	25	1.22	363	0.230	<1	2.52	0.011	1.32	<0.1	<0.01	7.7	0.6	<0.05	12	<0.5	<0.2
1418713	Soil	41	13	1.15	304	0.174	1	2.19	0.010	0.64	<0.1	0.01	6.7	0.4	<0.05	11	<0.5	<0.2
1418721	Soil	29	20	0.94	209	0.100	<1	2.06	0.010	0.52	0.1	0.02	5.3	0.3	<0.05	10	<0.5	<0.2
1418714	Soil	19	26	0.50	276	0.080	1	1.27	0.021	0.13	0.4	0.04	4.4	0.1	<0.05	4	<0.5	0.3
1418715	Soil	36	22	0.99	206	0.201	<1	2.21	0.010	1.24	0.6	<0.01	4.6	0.6	<0.05	11	<0.5	<0.2
1418722	Soil	18	16	0.56	223	0.090	<1	1.48	0.010	0.49	<0.1	0.02	5.3	0.2	<0.05	7	<0.5	<0.2
1418709	Soil	35	26	0.55	271	0.066	<1	1.76	0.012	0.24	0.4	0.02	6.9	0.1	<0.05	7	<0.5	<0.2
1418712	Soil	19	19	0.25	345	0.041	<1	1.11	0.009	0.20	0.4	0.01	3.3	<0.1	<0.05	4	<0.5	<0.2
1418711	Soil	57	17	1.16	268	0.232	<1	2.46	0.010	1.03	<0.1	<0.01	5.6	0.6	<0.05	12	<0.5	<0.2
1418718	Soil	42	15	0.43	278	0.054	<1	1.51	0.024	0.34	<0.1	0.04	2.9	0.5	0.20	5	3.7	<0.2
1418716	Soil	73	16	1.34	464	0.202	<1	2.61	0.010	1.27	0.1	0.01	7.3	0.5	<0.05	11	<0.5	<0.2
1418719	Soil	35	30	0.93	404	0.186	1	2.41	0.009	1.13	0.2	<0.01	6.3	0.6	<0.05	9	0.5	0.3
1368494	Soil	21	27	0.59	307	0.083	3	1.31	0.030	0.16	0.2	0.03	5.1	0.1	<0.05	5	0.6	<0.2
1368497	Soil	58	18	0.63	234	0.066	<1	2.02	0.009	0.45	0.2	0.01	6.0	0.3	<0.05	8	<0.5	<0.2
1368498	Soil	49	23	1.18	281	0.138	1	2.23	0.013	0.49	0.1	0.02	7.7	0.3	<0.05	10	<0.5	<0.2
1418710	Soil	22	18	0.72	220	0.056	<1	2.18	0.009	0.28	0.2	0.01	6.8	0.2	<0.05	10	<0.5	<0.2
1368492	Soil	14	26	0.80	285	0.083	3	1.17	0.042	0.12	0.3	0.01	4.0	<0.1	<0.05	4	0.5	<0.2
1368495	Soil	24	24	0.54	283	0.073	2	1.28	0.027	0.18	0.2	0.03	4.3	0.1	<0.05	4	0.5	<0.2
1368496	Soil	30	16	0.65	584	0.050	3	1.14	0.019	0.28	0.2	0.04	4.0	0.1	<0.05	4	0.6	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 4 of 9 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte Unit MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	1	2	0.01	0.001	
1418717	Soil	1.4	371.6	26.1	326	<0.1	7.7	11.8	635	6.35	10.3	5.6	6.3	20.2	39	0.5	0.2	4.1	76	0.30	0.096
1368490	Soil	0.4	36.7	60.9	115	<0.1	16.4	13.4	601	5.53	7.8	1.3	25.4	27.5	32	<0.1	0.4	1.2	70	0.69	0.120
1368491	Soil	1.0	28.8	11.7	85	<0.1	17.8	9.3	422	2.77	8.1	1.3	2.0	6.3	32	0.2	0.5	0.3	54	0.54	0.070
1368493	Soil	0.9	38.3	11.9	80	0.1	22.5	10.1	562	2.78	6.3	2.7	5.3	10.1	44	0.4	0.5	0.4	50	0.91	0.074
1368488	Soil	0.8	12.3	11.5	52	<0.1	11.2	7.1	352	2.66	5.5	0.6	2.2	5.3	18	0.1	0.3	0.1	53	0.29	0.051
1368489	Soil	0.5	25.0	38.6	76	<0.1	18.0	12.3	796	3.94	11.4	1.2	8.2	18.1	23	0.3	0.4	0.3	59	0.37	0.094
1368484	Soil	0.5	23.6	24.9	63	<0.1	19.7	10.0	309	2.88	8.8	1.3	8.9	5.4	32	<0.1	0.4	0.3	52	0.50	0.080
1368486	Soil	1.4	18.8	22.2	64	0.1	18.7	8.9	347	2.75	8.1	1.7	7.5	8.0	33	<0.1	0.5	0.2	55	0.45	0.067
1368487	Soil	0.6	14.6	24.0	54	<0.1	13.5	7.5	241	2.79	7.7	1.0	4.3	6.4	26	<0.1	0.4	0.4	57	0.37	0.041
1368479	Soil	1.1	30.9	15.2	88	<0.1	27.1	11.0	682	3.58	10.1	0.7	4.1	16.5	31	0.1	0.5	0.1	53	0.59	0.058
1368483	Soil	0.4	20.2	14.1	115	<0.1	13.0	14.7	763	4.85	4.0	0.9	1.4	23.8	21	<0.1	0.2	0.1	53	0.46	0.137
1368485	Soil	0.5	17.4	22.3	65	0.1	14.7	8.5	359	2.85	5.7	1.2	61.4	6.2	33	0.1	0.4	0.2	54	0.58	0.087
1368478	Soil	0.7	22.9	9.3	120	<0.1	10.9	15.2	784	5.25	4.9	2.0	<0.5	37.0	32	0.1	0.2	0.4	62	0.77	0.164
1368480	Soil	0.8	31.2	19.2	70	0.1	14.6	10.7	794	3.59	19.9	1.5	21.8	16.0	25	0.1	0.6	0.2	38	0.57	0.088
1368482	Soil	0.7	18.1	28.7	116	<0.1	14.2	14.0	765	4.75	5.0	1.1	0.6	20.6	23	0.3	0.5	0.4	56	0.42	0.101
1335975	Soil	1.0	11.0	10.8	64	<0.1	14.0	8.2	586	2.53	5.4	0.9	0.9	4.4	17	0.1	0.3	0.1	52	0.23	0.041
1368477	Soil	0.9	31.6	10.0	67	<0.1	23.3	10.5	320	2.74	11.0	1.2	7.8	6.0	41	0.3	0.6	0.4	58	0.79	0.111
1368476	Soil	1.0	36.5	8.4	72	0.1	29.4	11.0	437	2.57	10.0	0.7	2.0	3.9	50	0.4	0.7	0.2	55	1.51	0.094
1368481	Soil	0.6	35.5	15.6	57	<0.1	31.9	9.7	325	3.12	13.9	1.1	4.6	7.4	28	<0.1	0.7	0.2	62	0.44	0.061
1335974	Soil	1.0	14.1	16.2	152	<0.1	22.9	18.1	709	5.39	5.9	1.9	1.1	9.0	20	<0.1	0.3	0.1	108	0.39	0.071
1335973	Soil	1.0	14.8	13.6	108	<0.1	15.3	12.4	736	4.04	7.3	0.8	2.0	7.2	18	0.2	0.5	0.2	73	0.26	0.084
1335971	Soil	0.8	18.6	8.8	55	<0.1	20.0	9.5	250	2.75	9.8	0.8	15.8	5.9	19	<0.1	0.5	0.2	54	0.21	0.041
1335972	Soil	0.9	14.0	8.4	83	<0.1	16.7	10.7	923	3.43	8.0	0.6	1.1	4.8	19	0.1	0.5	0.1	63	0.28	0.067
1335970	Soil	1.0	9.2	8.5	76	<0.1	8.2	8.6	702	3.36	4.6	0.7	0.8	6.6	16	0.2	0.2	0.2	60	0.22	0.084
1335968	Soil	0.8	16.9	13.1	56	<0.1	15.8	8.5	287	2.69	8.7	1.0	2.9	7.5	24	<0.1	0.3	0.2	53	0.32	0.048
1335969	Soil	0.5	8.9	7.6	66	<0.1	7.8	7.4	449	3.27	4.4	0.7	<0.5	8.0	14	<0.1	0.2	0.1	54	0.21	0.047
1335967	Soil	0.9	20.2	15.3	57	<0.1	16.7	9.4	290	2.65	9.7	1.4	5.7	8.3	23	<0.1	0.5	0.2	53	0.30	0.041
1335966	Soil	0.8	15.9	18.1	65	<0.1	13.0	9.3	413	2.80	8.4	1.1	1.2	8.1	25	<0.1	0.3	0.2	57	0.37	0.058
1335965	Soil	0.7	27.1	11.2	94	<0.1	23.7	12.5	748	4.12	8.4	1.5	<0.5	24.5	22	<0.1	0.4	<0.1	61	0.43	0.080
1335964	Soil	0.8	22.3	10.3	68	<0.1	23.9	11.1	599	3.26	10.6	1.0	2.7	11.7	23	<0.1	0.5	0.1	61	0.36	0.056

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 4 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1418717	Soil	38	15	1.36	453	0.216	<1	3.12	0.012	1.56	<0.1	<0.01	10.8	1.0	<0.05	11	1.7	<0.2
1368490	Soil	89	33	1.09	465	0.070	<1	2.86	0.008	0.55	0.1	0.02	10.0	0.3	<0.05	12	<0.5	<0.2
1368491	Soil	21	27	0.56	319	0.088	1	1.50	0.022	0.12	0.3	0.04	4.8	0.1	<0.05	5	<0.5	<0.2
1368493	Soil	35	27	0.57	336	0.082	3	1.55	0.025	0.25	0.2	0.04	6.1	0.2	<0.05	5	<0.5	<0.2
1368488	Soil	18	21	0.50	176	0.072	1	1.67	0.010	0.09	0.2	0.02	3.9	<0.1	<0.05	7	<0.5	<0.2
1368489	Soil	55	27	0.58	313	0.056	2	2.00	0.010	0.27	0.4	0.01	6.5	0.2	<0.05	7	<0.5	<0.2
1368484	Soil	21	31	0.60	261	0.088	1	1.64	0.018	0.09	0.2	0.02	5.4	<0.1	<0.05	6	<0.5	<0.2
1368486	Soil	26	35	0.49	290	0.092	<1	1.77	0.015	0.09	0.3	0.02	6.0	<0.1	<0.05	6	<0.5	<0.2
1368487	Soil	19	29	0.51	213	0.067	<1	1.78	0.012	0.05	0.2	0.03	5.1	<0.1	<0.05	7	<0.5	<0.2
1368479	Soil	29	23	0.81	311	0.095	1	1.87	0.021	0.40	0.1	0.02	6.3	0.2	<0.05	8	<0.5	<0.2
1368483	Soil	50	18	1.07	322	0.105	<1	2.33	0.009	0.86	<0.1	<0.01	4.9	0.3	<0.05	12	<0.5	<0.2
1368485	Soil	24	23	0.64	231	0.089	<1	1.65	0.021	0.12	0.2	0.03	4.7	0.1	<0.05	6	<0.5	<0.2
1368478	Soil	85	17	1.13	307	0.188	2	2.45	0.015	1.15	<0.1	0.01	9.5	0.5	<0.05	12	<0.5	<0.2
1368480	Soil	54	15	0.52	321	0.015	1	1.73	0.010	0.27	0.2	0.06	6.2	0.2	<0.05	6	<0.5	<0.2
1368482	Soil	47	19	0.96	214	0.118	1	2.30	0.008	1.00	0.1	0.02	5.3	0.5	<0.05	10	<0.5	<0.2
1335975	Soil	16	24	0.34	245	0.037	1	1.25	0.008	0.08	0.3	0.01	3.5	<0.1	<0.05	5	<0.5	<0.2
1368477	Soil	20	29	0.56	305	0.088	4	1.08	0.027	0.12	0.6	0.04	4.3	0.1	<0.05	4	0.6	<0.2
1368476	Soil	14	29	0.86	266	0.078	2	1.22	0.036	0.09	0.2	0.05	4.4	0.1	<0.05	4	0.9	<0.2
1368481	Soil	26	36	0.54	237	0.093	2	1.44	0.020	0.13	0.2	0.05	7.1	0.1	<0.05	5	<0.5	<0.2
1335974	Soil	48	35	1.53	264	0.154	2	2.79	0.012	1.29	0.4	0.03	11.0	0.6	<0.05	11	<0.5	<0.2
1335973	Soil	20	28	0.74	237	0.063	2	2.10	0.010	0.10	0.1	0.04	8.2	0.1	<0.05	9	<0.5	<0.2
1335971	Soil	16	32	0.51	193	0.083	1	1.42	0.011	0.14	0.2	0.03	4.9	0.2	<0.05	5	<0.5	<0.2
1335972	Soil	17	27	0.71	287	0.097	2	1.94	0.012	0.17	0.2	0.01	7.0	0.1	<0.05	8	<0.5	<0.2
1335970	Soil	13	14	0.76	161	0.168	2	1.77	0.009	0.47	0.2	0.02	5.2	0.3	<0.05	10	<0.5	<0.2
1335968	Soil	28	25	0.52	261	0.086	<1	1.58	0.012	0.09	0.2	0.03	4.6	0.1	<0.05	6	<0.5	<0.2
1335969	Soil	14	12	0.64	162	0.131	1	1.79	0.009	0.28	0.4	0.02	5.0	0.2	<0.05	8	<0.5	<0.2
1335967	Soil	30	32	0.49	302	0.076	<1	1.57	0.013	0.06	0.2	0.02	5.7	<0.1	<0.05	5	<0.5	<0.2
1335966	Soil	25	27	0.55	284	0.104	<1	1.54	0.013	0.11	0.3	0.04	5.1	<0.1	<0.05	7	<0.5	<0.2
1335965	Soil	54	28	0.98	252	0.199	2	2.08	0.013	0.85	0.2	<0.01	7.9	0.4	<0.05	9	<0.5	<0.2
1335964	Soil	30	35	0.67	219	0.124	2	1.67	0.016	0.36	0.2	0.03	7.2	0.2	<0.05	6	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 5 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte	Unit	MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	
			Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	%
			ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
			0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
1335963	Soil		1.2	74.9	22.8	113	0.2	16.5	11.7	611	3.62	7.2	1.4	1.1	11.2	38	0.2	0.4	1.2	60	0.56	0.065	
1335960	Soil		0.7	35.3	12.0	108	<0.1	17.4	12.7	616	4.23	8.9	1.6	19.4	28.3	23	<0.1	0.4	0.3	56	0.47	0.113	
1335961	Soil		1.1	51.8	11.5	63	0.2	31.8	12.2	531	2.77	10.5	0.7	3.4	4.9	48	0.1	0.6	0.4	58	1.71	0.065	
1335962	Soil		0.8	39.9	10.3	82	<0.1	20.3	11.8	608	3.51	7.2	1.2	8.0	11.7	29	<0.1	0.5	0.9	68	0.60	0.114	
1335959	Soil		1.5	18.3	21.7	60	<0.1	23.0	11.2	283	2.74	11.7	0.5	14.7	4.3	24	0.2	0.5	0.4	62	0.33	0.024	
1335957	Soil		0.9	29.1	10.4	84	<0.1	25.2	12.6	453	3.51	10.1	1.1	<0.5	12.3	22	<0.1	0.5	0.3	68	0.30	0.044	
1335951	Soil		1.0	27.7	9.5	69	0.1	22.1	9.8	412	2.25	7.9	1.0	5.1	3.2	46	0.4	0.7	0.2	46	0.91	0.069	
1335954	Soil		0.7	35.9	11.0	85	0.1	18.4	9.6	478	3.18	7.1	0.9	3.9	11.0	52	0.2	0.5	0.4	57	0.97	0.085	
1418743	Soil		0.6	67.4	22.6	87	<0.1	21.1	13.4	651	4.04	7.5	1.4	4.8	13.9	32	0.1	0.5	0.2	61	0.59	0.094	
1418741	Soil		0.6	13.5	11.6	124	<0.1	16.7	17.9	772	5.68	6.2	1.4	0.9	26.6	21	<0.1	0.4	0.1	57	0.48	0.134	
1335956	Soil		0.8	45.4	7.4	120	<0.1	19.7	13.1	808	4.59	6.6	1.6	2.5	27.0	19	<0.1	0.3	0.8	64	0.39	0.102	
1335953	Soil		0.9	34.4	10.8	68	0.1	20.6	10.1	789	2.53	6.1	2.1	5.0	5.4	55	0.4	0.5	0.4	49	1.13	0.074	
1418748	Soil		0.4	42.2	9.7	90	0.1	19.5	11.9	723	3.50	6.4	2.0	6.4	18.5	131	0.2	0.5	<0.1	49	7.26	0.105	
1418746	Soil		0.7	33.0	38.8	54	<0.1	19.8	7.8	475	2.18	9.3	1.2	25.7	7.2	22	<0.1	0.4	0.3	35	0.39	0.047	
1335955	Soil		1.0	35.1	11.5	182	<0.1	12.4	16.0	818	5.44	5.9	1.8	1.6	31.6	25	0.2	0.3	0.3	76	0.67	0.168	
1335952	Soil		0.9	28.6	10.6	73	<0.1	21.8	10.0	381	2.35	8.2	0.8	3.4	3.4	37	0.3	0.6	0.5	50	0.74	0.076	
1418744	Soil		0.5	28.7	12.4	60	<0.1	20.8	9.9	474	2.76	9.4	0.8	3.7	7.7	34	0.2	0.6	0.1	55	0.66	0.097	
1418742	Soil		1.0	14.0	15.0	71	<0.1	19.1	10.8	339	2.91	8.0	0.6	0.5	7.2	23	0.2	0.5	0.2	56	0.32	0.042	
1335958	Soil		1.3	40.9	12.5	92	<0.1	21.8	12.4	581	3.71	8.8	1.3	3.7	10.5	32	0.2	0.6	0.8	69	0.42	0.045	
1418735	Soil		0.5	16.7	43.7	78	<0.1	10.9	9.8	428	3.59	6.4	0.8	4.2	9.1	32	0.1	0.4	0.6	60	0.52	0.103	
1418745	Soil		0.5	19.7	26.3	108	<0.1	13.0	13.1	765	3.78	5.7	1.0	15.2	14.2	63	0.3	0.4	0.3	52	2.53	0.104	
1418747	Soil		0.6	21.5	30.7	104	<0.1	30.9	13.5	833	3.97	4.7	1.1	9.2	22.6	37	0.2	0.4	0.2	27	0.76	0.100	
1418737	Soil		0.7	27.7	25.8	106	<0.1	14.1	14.3	741	5.01	6.0	1.1	6.4	16.1	38	<0.1	0.5	0.4	66	0.60	0.156	
1418730	Soil		1.1	14.8	38.6	88	<0.1	14.5	11.7	739	3.47	6.7	1.2	4.0	10.6	46	0.1	0.3	0.5	56	0.50	0.093	
1418732	Soil		0.7	13.8	22.8	61	<0.1	14.8	8.1	298	3.01	6.8	0.7	4.2	6.1	31	<0.1	0.3	0.4	53	0.40	0.060	
1418736	Soil		0.3	28.6	28.3	126	<0.1	15.4	17.9	871	5.45	4.1	1.8	5.9	23.2	54	0.2	0.3	0.3	67	0.92	0.226	
1418738	Soil		0.5	38.0	24.3	133	<0.1	16.7	18.2	762	6.27	4.8	1.1	3.5	19.0	38	<0.1	0.3	0.3	87	0.82	0.238	
1418733	Soil		0.5	13.9	44.3	93	<0.1	12.7	14.5	735	4.77	6.2	0.9	1.8	11.6	28	0.5	0.4	0.8	63	0.56	0.143	
1418739	Soil		0.7	27.2	10.8	117	<0.1	16.0	15.5	826	4.39	6.4	1.2	1.6	17.0	28	0.1	0.5	0.2	56	0.44	0.102	
1418726	Soil		0.7	27.7	25.8	69	0.1	19.5	9.9	401	2.93	8.2	1.3	12.4	6.9	40	<0.1	0.5	0.5	57	0.56	0.078	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 5 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1335963	Soil	32	27	0.77	395	0.141	2	1.96	0.016	0.55	0.3	0.02	6.1	0.3	<0.05	7	<0.5	<0.2
1335960	Soil	79	22	0.85	290	0.146	<1	2.13	0.011	0.80	<0.1	0.04	8.2	0.5	<0.05	10	0.9	<0.2
1335961	Soil	20	31	0.66	329	0.084	2	1.41	0.026	0.14	0.2	0.05	5.1	0.1	<0.05	4	<0.5	<0.2
1335962	Soil	39	28	0.84	254	0.127	1	1.69	0.022	0.42	0.2	0.03	6.1	0.2	<0.05	6	<0.5	<0.2
1335959	Soil	12	37	0.42	421	0.070	1	1.76	0.009	0.13	0.1	0.02	5.4	0.1	<0.05	5	<0.5	<0.2
1335957	Soil	22	39	0.70	262	0.127	2	1.96	0.014	0.37	0.2	0.03	7.1	0.2	<0.05	7	<0.5	<0.2
1335951	Soil	15	25	0.49	348	0.061	3	1.24	0.024	0.08	0.2	0.05	4.0	<0.1	<0.05	4	<0.5	<0.2
1335954	Soil	35	26	0.73	348	0.097	3	1.55	0.023	0.42	0.2	0.04	5.7	0.2	<0.05	6	0.6	<0.2
1418743	Soil	51	28	0.81	328	0.093	2	2.03	0.013	0.44	0.3	0.03	7.4	0.2	<0.05	8	<0.5	<0.2
1418741	Soil	41	22	1.17	345	0.085	<1	2.66	0.008	0.74	0.1	<0.01	7.1	0.4	<0.05	12	<0.5	<0.2
1335956	Soil	43	30	1.10	258	0.208	1	2.29	0.010	1.02	<0.1	0.02	9.1	0.5	<0.05	11	<0.5	<0.2
1335953	Soil	32	25	0.55	326	0.073	3	1.36	0.023	0.22	0.2	0.05	5.0	0.1	<0.05	4	1.0	<0.2
1418748	Soil	44	15	1.06	391	0.145	2	1.68	0.023	0.46	<0.1	0.05	6.8	0.4	<0.05	8	<0.5	<0.2
1418746	Soil	25	16	0.32	227	0.018	<1	1.15	0.010	0.15	0.3	0.06	5.1	0.1	<0.05	5	0.7	<0.2
1335955	Soil	38	24	1.17	299	0.237	2	2.44	0.013	1.29	0.2	0.02	6.5	0.6	<0.05	13	0.9	<0.2
1335952	Soil	15	27	0.54	269	0.077	3	1.24	0.028	0.09	0.3	0.04	4.4	<0.1	<0.05	4	0.6	<0.2
1418744	Soil	25	25	0.58	235	0.079	3	1.24	0.026	0.15	0.3	0.02	4.8	0.1	<0.05	5	<0.5	<0.2
1418742	Soil	18	32	0.53	224	0.066	2	1.70	0.008	0.30	0.2	<0.01	4.6	0.1	<0.05	6	0.6	<0.2
1335958	Soil	31	34	0.81	365	0.120	2	2.02	0.011	0.43	0.2	0.03	6.8	0.3	<0.05	7	<0.5	<0.2
1418735	Soil	28	21	0.75	208	0.069	<1	1.82	0.013	0.16	0.2	0.01	4.4	0.1	<0.05	8	<0.5	<0.2
1418745	Soil	47	14	0.66	424	0.034	1	1.64	0.014	0.35	0.2	0.02	7.5	0.3	<0.05	7	<0.5	<0.2
1418747	Soil	58	32	0.68	311	0.008	2	1.77	0.010	0.25	0.2	0.02	4.8	0.3	<0.05	5	<0.5	<0.2
1418737	Soil	58	25	1.04	300	0.090	2	2.47	0.008	0.48	0.2	<0.01	5.7	0.2	<0.05	11	<0.5	<0.2
1418730	Soil	30	24	0.66	215	0.105	2	1.75	0.011	0.22	0.3	<0.01	3.8	0.1	<0.05	8	<0.5	<0.2
1418732	Soil	19	24	0.60	186	0.051	<1	1.78	0.015	0.12	0.2	<0.01	3.5	<0.1	<0.05	6	<0.5	<0.2
1418736	Soil	55	24	1.28	311	0.114	1	2.57	0.012	0.59	0.1	<0.01	5.6	0.3	<0.05	12	<0.5	<0.2
1418738	Soil	62	35	1.54	368	0.091	<1	3.02	0.009	0.41	0.1	<0.01	8.4	0.2	<0.05	13	<0.5	<0.2
1418733	Soil	29	22	1.08	324	0.045	<1	2.33	0.009	0.14	0.2	<0.01	5.6	<0.1	<0.05	10	<0.5	<0.2
1418739	Soil	33	23	0.95	310	0.103	2	2.19	0.009	0.59	0.1	0.01	5.6	0.3	<0.05	10	<0.5	<0.2
1418726	Soil	22	28	0.62	256	0.095	2	1.48	0.022	0.14	0.2	0.02	5.4	0.1	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 6 of 9 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte	Unit	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%
		MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL	MDL
1418729	Soil	0.9	19.6	20.9	66	<0.1	17.2	8.8	283	2.73	9.7	1.5	8.1	7.4	35	0.2	0.5	0.3	53	0.42	0.070
1418731	Soil	1.0	16.3	27.7	65	0.1	15.6	8.8	470	2.95	7.8	1.0	3.5	6.7	40	0.1	0.3	0.4	56	0.49	0.059
1418740	Soil	0.9	20.1	15.4	81	<0.1	14.2	10.6	604	3.07	6.9	0.8	6.1	15.2	28	0.2	0.5	0.2	51	0.38	0.085
1390490	Soil	1.2	31.7	19.4	72	0.2	22.4	9.1	544	2.51	8.3	2.0	7.4	6.2	57	0.3	0.5	0.4	48	0.96	0.080
1418728	Soil	1.2	19.0	19.0	60	0.1	17.8	9.4	376	2.60	8.3	1.4	13.7	6.4	39	0.2	0.5	0.3	54	0.53	0.078
1418734	Soil	0.6	23.6	149.3	100	0.2	16.5	11.4	1065	4.66	9.5	1.9	133.6	20.1	39	0.4	0.6	1.3	64	0.66	0.154
1418727	Soil	1.2	33.1	24.7	59	0.2	19.8	11.2	409	2.69	7.7	1.6	7.6	6.0	47	0.2	0.5	0.3	58	0.63	0.062
1348977	Soil	0.9	13.4	33.8	57	<0.1	11.2	8.2	244	2.98	6.4	0.9	522.8	5.1	34	0.1	0.3	0.4	57	0.49	0.086
1348978	Soil	0.7	14.0	62.1	100	<0.1	7.3	11.4	594	4.32	4.7	1.0	1.7	5.5	37	0.2	0.2	1.1	68	0.80	0.189
1348986	Soil	1.0	12.1	9.7	49	<0.1	11.4	6.7	338	2.36	5.0	0.5	2.4	5.5	13	<0.1	0.3	0.2	47	0.16	0.048
1335976	Soil	1.1	23.8	19.6	68	<0.1	17.5	10.8	429	3.19	9.4	2.0	10.4	12.5	33	<0.1	0.5	0.3	61	0.45	0.057
1348984	Soil	0.7	8.4	17.4	47	<0.1	5.3	4.2	271	1.99	2.4	0.5	2.2	2.8	15	0.1	0.1	0.3	36	0.21	0.070
1348979	Soil	0.9	16.8	66.6	106	<0.1	11.1	13.4	615	4.48	5.6	1.1	12.9	11.4	31	0.2	0.3	2.2	66	0.68	0.189
1348985	Soil	0.9	13.1	13.8	52	<0.1	12.8	7.6	321	3.03	5.9	0.7	2.6	6.9	24	<0.1	0.3	0.2	60	0.29	0.042
1418750	Soil	0.8	20.2	15.7	59	<0.1	14.6	8.4	310	2.83	7.1	1.2	3.5	10.0	29	<0.1	0.5	0.3	52	0.41	0.056
1348983	Soil	1.0	13.6	15.2	51	<0.1	12.9	7.2	257	2.51	6.4	0.7	1.3	5.8	23	<0.1	0.3	0.2	50	0.30	0.052
1348981	Soil	1.1	18.5	27.8	62	<0.1	17.8	10.5	610	3.06	8.3	1.3	10.8	8.3	41	0.1	0.5	0.3	61	0.58	0.075
1348982	Soil	0.8	13.1	28.2	53	<0.1	12.4	7.3	291	2.44	7.4	1.2	10.4	7.8	28	<0.1	0.3	0.4	48	0.37	0.064
1418749	Soil	1.1	24.1	16.9	64	<0.1	17.5	9.1	382	2.97	7.3	1.6	15.9	12.2	31	0.1	0.5	0.3	56	0.45	0.061
1348987	Soil	0.9	14.3	30.9	71	<0.1	8.2	7.8	646	3.28	5.0	0.7	5.3	4.5	15	0.2	0.2	0.4	51	0.24	0.154
1348976	Soil	0.8	15.6	38.6	75	<0.1	11.8	9.3	419	3.45	6.2	1.2	7.6	6.0	42	<0.1	0.4	0.5	58	0.60	0.080
1348980	Soil	0.8	23.6	21.2	67	0.1	18.2	10.1	475	3.11	8.0	1.5	15.5	7.4	46	0.2	0.4	0.3	64	0.69	0.106
1335981	Soil	0.9	16.7	17.3	103	<0.1	15.6	13.9	916	4.73	6.8	2.2	3.4	23.4	18	0.1	0.4	0.3	70	0.25	0.072
1335977	Soil	1.1	18.0	17.8	56	<0.1	15.8	8.1	274	2.81	7.4	1.2	8.1	11.2	25	<0.1	0.6	0.3	54	0.29	0.034
1335984	Soil	0.9	40.0	12.4	115	<0.1	15.2	8.8	615	3.27	5.6	0.9	10.0	9.2	16	0.2	0.4	0.4	54	0.17	0.040
1418701	Soil	2.4	16.7	21.5	97	0.2	14.2	11.9	912	3.99	22.6	1.5	76.6	18.9	30	0.2	0.5	0.5	59	0.47	0.060
1418705	Soil	1.1	38.9	32.1	116	<0.1	13.6	12.4	671	4.18	3.7	1.6	3.0	31.1	47	0.2	0.2	0.5	58	1.42	0.103
1348996	Soil	0.9	62.7	11.0	82	0.2	23.0	8.9	466	2.46	5.9	1.4	2.8	5.4	50	0.5	0.4	0.6	50	0.83	0.070
1335985	Soil	1.0	34.9	16.4	67	<0.1	20.8	9.9	501	3.04	7.4	1.2	3.1	10.2	27	<0.1	0.5	0.7	58	0.32	0.037
1418703	Soil	1.0	23.5	9.5	70	<0.1	20.2	9.7	399	2.82	12.3	1.1	13.5	6.3	41	0.2	0.6	0.4	55	0.75	0.107

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 6 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1418729	Soil	25	27	0.50	258	0.070	<1	1.42	0.018	0.07	0.2	0.02	4.7	<0.1	<0.05	5	<0.5	<0.2
1418731	Soil	24	27	0.58	232	0.062	2	1.59	0.017	0.10	0.2	0.02	4.6	<0.1	<0.05	6	<0.5	<0.2
1418740	Soil	32	23	0.46	312	0.033	1	1.60	0.009	0.18	0.1	0.01	4.6	0.1	<0.05	6	0.6	<0.2
1390490	Soil	22	25	0.50	302	0.065	2	1.23	0.023	0.13	0.2	0.03	4.5	<0.1	<0.05	4	<0.5	<0.2
1418728	Soil	24	28	0.50	255	0.074	2	1.32	0.018	0.06	0.3	0.04	4.8	<0.1	<0.05	5	<0.5	<0.2
1418734	Soil	54	22	0.51	337	0.019	<1	1.67	0.011	0.14	0.5	0.03	10.7	<0.1	<0.05	7	<0.5	<0.2
1418727	Soil	26	30	0.54	299	0.084	3	1.50	0.021	0.07	0.2	0.04	5.4	<0.1	<0.05	6	<0.5	<0.2
1348977	Soil	17	19	0.51	173	0.085	2	1.48	0.013	0.12	0.2	0.01	4.3	<0.1	<0.05	6	<0.5	<0.2
1348978	Soil	15	12	0.89	200	0.179	1	2.01	0.015	0.56	0.1	<0.01	6.0	0.2	<0.05	9	<0.5	<0.2
1348986	Soil	17	19	0.44	124	0.051	1	1.38	0.008	0.12	0.4	0.01	3.1	<0.1	<0.05	6	<0.5	<0.2
1335976	Soil	40	32	0.58	313	0.110	<1	1.85	0.014	0.17	0.2	0.04	7.8	0.1	<0.05	7	<0.5	<0.2
1348984	Soil	16	11	0.35	130	0.031	<1	1.17	0.008	0.12	0.1	0.01	2.9	<0.1	<0.05	5	<0.5	<0.2
1348979	Soil	28	19	0.95	201	0.134	<1	2.30	0.009	0.79	0.3	0.02	4.4	0.4	<0.05	10	<0.5	<0.2
1348985	Soil	27	26	0.59	221	0.065	1	1.95	0.009	0.11	0.1	<0.01	4.6	<0.1	<0.05	7	<0.5	<0.2
1418750	Soil	26	25	0.55	260	0.085	1	1.59	0.013	0.14	0.2	0.01	4.8	0.1	<0.05	6	<0.5	<0.2
1348983	Soil	22	23	0.49	173	0.057	1	1.54	0.010	0.07	0.2	<0.01	3.8	<0.1	<0.05	6	<0.5	<0.2
1348981	Soil	27	30	0.56	287	0.095	2	1.72	0.019	0.10	0.3	0.04	5.6	<0.1	<0.05	6	<0.5	<0.2
1348982	Soil	25	24	0.42	194	0.062	<1	1.30	0.013	0.08	0.3	0.02	4.7	<0.1	<0.05	5	<0.5	<0.2
1418749	Soil	36	30	0.57	281	0.100	1	1.68	0.016	0.17	0.2	0.02	5.9	0.1	<0.05	6	<0.5	<0.2
1348987	Soil	24	16	0.49	176	0.027	1	1.68	0.007	0.21	0.2	0.02	4.5	0.1	<0.05	7	<0.5	<0.2
1348976	Soil	22	19	0.70	190	0.120	<1	1.81	0.019	0.16	0.2	0.04	5.8	<0.1	<0.05	7	<0.5	<0.2
1348980	Soil	27	29	0.70	282	0.085	2	1.72	0.025	0.08	0.2	0.03	6.2	<0.1	<0.05	6	<0.5	<0.2
1335981	Soil	41	28	1.01	285	0.214	2	2.35	0.009	0.99	0.1	0.02	7.5	0.4	<0.05	10	<0.5	<0.2
1335977	Soil	37	30	0.53	238	0.090	<1	1.73	0.010	0.13	0.2	0.01	5.3	0.1	<0.05	6	<0.5	<0.2
1335984	Soil	20	24	0.73	335	0.121	2	1.76	0.009	0.48	0.1	0.03	5.3	0.3	<0.05	7	<0.5	<0.2
1418701	Soil	53	24	0.70	338	0.115	3	1.99	0.010	0.71	0.2	0.05	7.4	0.3	<0.05	8	<0.5	<0.2
1418705	Soil	63	19	1.04	337	0.195	<1	2.05	0.017	0.96	<0.1	0.03	4.9	0.5	<0.05	10	<0.5	<0.2
1348996	Soil	25	29	0.62	392	0.081	2	1.43	0.021	0.19	0.1	0.06	5.4	0.1	<0.05	5	0.8	<0.2
1335985	Soil	39	32	0.65	338	0.111	1	1.68	0.014	0.36	0.2	0.04	6.0	0.2	<0.05	6	<0.5	<0.2
1418703	Soil	20	24	0.53	284	0.075	3	1.08	0.022	0.12	0.5	0.05	3.8	<0.1	<0.05	4	<0.5	0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 7 of 9 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte	Unit	MDL	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	
			Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
			ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
			0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	2	0.01	0.001	
1418707	Soil		1.7	54.0	34.9	121	<0.1	20.1	12.5	1267	4.40	10.7	2.1	15.9	32.3	26	0.4	0.7	1.0	54	0.51	0.083
1348997	Soil		1.8	20.5	18.6	83	<0.1	19.9	10.8	479	3.67	6.4	1.7	22.4	36.3	22	0.2	0.6	0.3	57	0.39	0.068
1335983	Soil		0.7	47.6	8.5	129	<0.1	13.8	13.4	671	5.11	4.4	1.8	9.6	31.9	21	0.2	0.3	0.6	76	0.39	0.130
1418704	Soil		1.7	23.9	16.9	113	<0.1	13.4	12.1	1116	4.21	5.6	2.0	3.6	26.8	37	0.4	0.6	1.0	54	0.66	0.115
1418614	Soil		1.3	23.3	66.9	139	<0.1	14.1	15.9	849	5.23	3.4	2.0	3.4	18.0	40	0.3	0.2	0.4	65	0.61	0.139
1348994	Soil		1.9	36.7	15.4	77	0.2	25.1	9.6	399	2.49	8.2	1.4	16.1	4.8	43	0.4	0.6	1.6	53	0.72	0.070
1418702	Soil		1.1	27.5	15.9	89	0.1	19.3	9.7	567	2.96	5.4	2.7	14.2	10.3	60	0.4	0.6	0.3	50	1.08	0.083
1418706	Soil		1.7	51.2	15.1	81	<0.1	25.5	11.6	635	3.06	9.7	1.3	7.5	8.1	39	0.1	0.7	3.3	57	0.58	0.077
1418613	Soil		1.5	18.0	15.8	60	0.1	19.2	8.8	411	2.35	7.0	1.5	6.6	6.1	39	0.2	0.4	0.3	50	0.53	0.080
1348995	Soil		2.0	43.4	14.5	82	0.2	28.2	10.6	457	2.73	7.9	1.2	11.9	5.9	45	0.4	0.6	1.1	56	0.74	0.075
1335982	Soil		1.0	45.1	12.4	102	<0.1	21.0	11.1	648	4.02	7.4	1.3	1.1	14.6	24	0.1	0.4	0.5	71	0.36	0.089
1335979	Soil		0.4	13.3	30.6	60	0.1	9.3	8.5	375	2.98	10.2	1.3	11.9	12.9	21	<0.1	0.4	0.4	40	0.29	0.052
1348993	Soil		1.0	35.2	18.3	85	0.2	22.7	10.5	499	2.70	8.2	1.2	4.1	5.1	41	0.2	0.7	1.4	56	0.67	0.066
1348989	Soil		0.8	41.9	21.5	107	<0.1	14.2	14.2	645	4.76	4.4	1.0	7.6	14.9	33	0.2	0.3	0.2	70	0.49	0.112
1335989	Soil		0.8	66.5	14.8	184	<0.1	17.0	14.4	1207	5.32	5.0	1.7	11.9	25.2	36	0.3	0.5	0.7	77	0.73	0.126
1335978	Soil		0.7	17.5	23.7	50	<0.1	14.7	6.9	221	2.54	6.9	0.8	11.8	8.1	17	<0.1	0.5	0.4	50	0.21	0.041
1348991	Soil		1.0	35.6	31.9	111	0.1	25.5	14.8	669	4.69	8.8	1.3	<0.5	20.8	30	0.2	0.6	0.4	82	0.37	0.087
1348988	Soil		1.1	25.8	21.5	84	<0.1	17.3	11.9	494	4.30	7.0	1.0	0.7	15.0	31	0.1	0.5	0.3	62	0.36	0.059
1335990	Soil		0.8	24.0	12.0	58	<0.1	24.3	10.7	456	2.80	9.0	0.8	10.2	6.7	30	0.2	0.6	0.3	56	0.35	0.030
1335987	Soil		1.8	160.0	41.7	231	0.1	14.1	10.2	497	4.12	10.6	6.1	20.8	14.9	39	0.2	0.4	4.7	45	0.24	0.036
1335980	Soil		1.2	22.2	63.9	94	0.4	10.3	11.2	718	4.57	95.6	3.6	43.9	25.2	22	0.5	0.8	1.7	53	0.33	0.101
1348990	Soil		0.7	37.1	9.7	112	<0.1	18.7	14.0	683	4.91	6.3	1.4	2.1	23.5	34	<0.1	0.5	0.1	73	0.47	0.113
1335992	Soil		1.0	39.4	13.0	127	<0.1	20.1	15.7	900	5.16	2.6	3.7	1.5	43.4	27	0.1	0.2	0.8	76	0.51	0.135
1335986	Soil		0.9	44.3	14.2	87	<0.1	16.5	7.8	297	2.67	10.3	0.8	0.7	6.8	23	0.1	0.5	0.8	50	0.24	0.026
1335988	Soil		2.1	348.9	21.2	170	0.1	16.5	25.6	518	5.31	17.3	5.4	1.6	18.7	34	0.2	0.6	1.8	54	0.24	0.042
1348992	Soil		0.8	44.2	13.6	111	<0.1	18.5	12.5	733	4.82	6.1	1.8	0.8	31.6	31	0.2	0.5	0.1	66	0.44	0.099
1418635	Soil		1.0	37.2	12.8	80	0.1	30.8	11.3	540	2.76	10.1	0.8	2.6	5.3	58	0.4	0.9	0.2	54	1.33	0.084
1418622	Soil		0.9	15.0	38.1	143	0.1	13.5	17.3	1358	5.54	3.2	2.0	18.7	30.4	34	0.2	0.3	0.4	58	0.68	0.153
1418624	Soil		1.2	25.5	94.0	105	0.3	17.5	11.8	776	4.04	6.3	2.0	14.5	19.9	40	0.2	0.4	1.3	54	0.66	0.108
1335993	Soil		1.0	41.2	8.5	83	<0.1	13.4	13.5	854	4.92	6.3	1.7	0.9	18.2	30	0.1	0.4	0.7	81	0.50	0.140

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 7 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.01	0.01	0.05	1	0.5	0.2	
1418707	Soil	66	21	0.56	413	0.076	4	1.94	0.010	0.63	0.1	0.18	9.3	0.6	<0.05	8	<0.5	0.2
1348997	Soil	30	31	0.79	173	0.119	3	1.84	0.009	0.59	0.1	0.16	8.5	0.3	<0.05	8	1.3	0.8
1335983	Soil	38	22	1.42	272	0.232	1	2.60	0.009	1.29	0.9	0.08	5.7	0.5	<0.05	12	0.9	0.4
1418704	Soil	84	21	0.93	342	0.088	2	1.99	0.011	0.82	0.1	0.08	6.6	0.4	<0.05	9	1.0	0.3
1418614	Soil	66	23	1.09	274	0.165	2	2.49	0.013	1.03	0.2	0.09	4.5	0.5	<0.05	12	0.9	0.4
1348994	Soil	18	31	0.54	300	0.080	3	1.35	0.022	0.09	0.3	0.12	5.2	<0.1	<0.05	4	1.5	0.6
1418702	Soil	38	24	0.62	352	0.075	3	1.47	0.019	0.31	0.2	0.09	5.5	0.1	<0.05	6	1.1	0.3
1418706	Soil	24	28	0.69	326	0.094	2	1.39	0.030	0.19	0.2	0.07	5.1	0.2	<0.05	5	0.7	0.3
1418613	Soil	23	31	0.46	266	0.074	2	1.38	0.018	0.06	0.3	0.05	4.5	<0.1	<0.05	4	0.7	<0.2
1348995	Soil	21	37	0.64	390	0.086	3	1.54	0.022	0.11	0.2	0.09	5.7	0.1	<0.05	5	1.5	0.5
1335982	Soil	31	33	1.24	311	0.130	2	2.37	0.010	0.42	0.1	0.03	5.5	0.3	<0.05	10	<0.5	<0.2
1335979	Soil	31	13	0.51	306	0.066	1	1.64	0.008	0.44	0.1	0.03	5.5	0.2	<0.05	6	0.6	<0.2
1348993	Soil	18	34	0.59	347	0.093	1	1.54	0.022	0.10	0.3	0.04	5.6	<0.1	<0.05	5	<0.5	0.2
1348989	Soil	30	23	1.19	337	0.191	1	2.50	0.008	0.73	<0.1	0.06	4.5	0.4	<0.05	10	1.3	0.2
1335989	Soil	70	24	1.37	580	0.234	1	2.58	0.014	1.03	0.1	0.08	7.3	0.6	<0.05	11	1.0	0.3
1335978	Soil	19	24	0.44	157	0.065	1	1.55	0.010	0.11	0.2	0.07	3.5	<0.1	<0.05	5	0.8	0.2
1348991	Soil	33	33	1.15	322	0.208	2	2.67	0.010	0.92	0.1	<0.01	8.3	0.4	<0.05	10	<0.5	<0.2
1348988	Soil	58	27	0.97	331	0.087	1	2.41	0.010	0.31	0.1	0.02	5.5	0.2	<0.05	9	<0.5	<0.2
1335990	Soil	25	32	0.51	351	0.088	3	1.49	0.017	0.19	0.2	0.07	5.9	<0.1	<0.05	5	0.8	0.2
1335987	Soil	39	38	0.83	281	0.115	2	2.13	0.010	0.62	0.1	0.15	6.6	0.6	<0.05	6	4.4	0.8
1335980	Soil	43	16	0.47	282	0.061	3	1.65	0.007	0.49	0.4	0.17	5.6	0.3	<0.05	7	1.9	1.6
1348990	Soil	64	27	1.35	304	0.143	1	2.61	0.008	0.69	0.1	0.04	7.2	0.3	<0.05	11	<0.5	<0.2
1335992	Soil	120	26	1.35	374	0.228	<1	2.59	0.009	1.29	<0.1	0.03	8.7	0.6	<0.05	12	<0.5	<0.2
1335986	Soil	16	24	0.58	263	0.105	2	1.45	0.010	0.28	0.1	0.02	4.0	0.2	<0.05	5	<0.5	<0.2
1335988	Soil	35	25	0.68	366	0.132	1	2.17	0.010	0.71	0.1	0.04	6.3	0.5	<0.05	8	2.3	<0.2
1348992	Soil	72	25	0.94	410	0.145	1	2.38	0.008	0.93	0.1	0.02	7.6	0.3	<0.05	10	<0.5	<0.2
1418635	Soil	19	29	0.72	439	0.076	2	1.34	0.028	0.08	0.3	0.04	4.7	<0.1	<0.05	4	<0.5	<0.2
1418622	Soil	88	16	1.20	378	0.182	1	2.47	0.010	1.14	0.1	0.01	7.4	0.7	<0.05	12	<0.5	<0.2
1418624	Soil	46	24	0.61	360	0.064	3	1.49	0.021	0.37	0.3	0.02	7.1	0.2	<0.05	6	<0.5	<0.2
1335993	Soil	45	19	1.25	479	0.234	2	2.52	0.014	1.28	0.1	0.02	8.0	0.5	<0.05	8	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 8 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method Analyte	Unit	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
MDL		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	%
		0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	2	0.01	0.001	
1418633	Soil	1.0	28.2	11.3	75	0.1	24.0	9.7	402	2.45	8.6	0.9	7.6	4.7	43	0.5	0.8	0.2	47	0.66	0.064
1418620	Soil	2.2	23.8	25.9	68	<0.1	14.7	11.2	1158	3.69	9.8	1.2	22.7	12.8	18	0.2	0.7	0.6	52	0.21	0.031
1418623	Soil	0.8	22.4	59.3	118	0.1	16.2	15.2	949	4.49	4.5	1.4	9.1	22.7	47	0.2	0.4	0.7	55	0.95	0.115
1335991	Soil	1.4	56.6	10.0	139	<0.1	12.8	12.3	671	4.61	3.0	2.6	5.4	22.7	28	0.2	0.3	0.8	67	0.64	0.143
1418625	Soil	1.0	25.1	22.1	70	0.2	21.1	9.6	454	2.76	8.8	1.2	14.8	8.0	43	0.1	0.5	0.3	51	0.74	0.096
1418618	Soil	1.1	15.0	16.9	103	<0.1	10.9	13.2	733	4.47	4.1	1.1	7.4	16.6	29	0.1	0.2	0.2	56	0.54	0.136
1418616	Soil	2.6	16.3	25.5	127	<0.1	11.8	14.6	884	4.07	3.5	1.3	15.2	19.4	40	0.2	0.2	0.3	49	0.56	0.123
1418708	Soil	1.2	42.3	13.0	75	0.1	24.7	9.8	473	2.66	7.4	1.1	6.2	6.3	66	0.3	0.6	0.5	49	1.37	0.082
1418621	Soil	1.3	26.2	22.4	101	<0.1	24.7	14.0	646	3.89	6.6	1.1	1.7	11.2	33	0.1	0.4	0.3	62	0.44	0.076
1418619	Soil	1.1	21.1	13.0	101	<0.1	17.2	14.6	926	4.51	4.3	1.5	7.8	24.7	30	<0.1	0.4	0.3	58	0.52	0.105
1418617	Soil	1.7	30.3	20.5	85	0.1	26.1	12.2	545	3.12	9.2	1.2	9.1	8.6	38	0.2	0.8	0.3	56	0.51	0.070
1418615	Soil	2.5	17.3	38.0	89	<0.1	12.5	12.4	666	3.38	4.8	1.0	2.5	10.1	38	0.2	0.3	0.4	54	0.43	0.097
1418626	Soil	1.4	20.3	121.8	80	0.5	16.0	11.1	504	3.38	55.9	2.5	89.5	12.5	36	0.2	0.6	2.1	55	0.52	0.094
1418632	Soil	0.9	25.8	11.2	62	<0.1	22.3	9.8	474	2.45	8.5	1.0	5.0	5.1	44	0.3	0.7	0.2	47	0.71	0.070
1418638	Soil	0.2	12.2	14.6	98	<0.1	10.5	13.0	762	4.22	2.1	1.7	2.9	19.5	31	0.2	0.1	0.2	49	0.59	0.127
1418634	Soil	1.0	30.1	11.3	65	0.1	26.0	10.6	442	2.50	8.9	1.0	3.9	5.3	47	0.4	0.8	0.2	49	0.83	0.070
1418631	Soil	1.3	21.3	18.0	67	0.1	19.2	10.1	468	2.81	7.8	1.3	6.2	7.3	40	0.1	0.6	0.4	55	0.54	0.077
1418627	Soil	1.0	18.6	38.1	83	<0.1	11.4	8.2	434	2.96	6.7	1.8	30.3	11.3	35	0.2	0.3	0.4	44	0.51	0.104
1418637	Soil	0.8	30.2	10.8	66	0.1	25.0	9.8	429	2.34	9.6	0.6	3.5	4.5	49	0.4	0.9	0.2	45	1.47	0.069
1418640	Soil	0.3	26.0	22.2	114	<0.1	14.5	14.3	843	4.04	3.5	1.1	4.1	19.8	25	0.2	0.3	0.2	51	0.56	0.113
1418629	Soil	0.5	16.6	31.6	86	<0.1	10.3	10.4	379	3.31	4.0	1.7	10.7	12.7	39	0.1	0.3	0.3	51	0.50	0.099
1418630	Soil	0.5	18.8	20.7	85	<0.1	12.7	9.9	402	3.14	5.8	1.8	8.2	9.8	38	0.1	0.3	0.3	50	0.58	0.106
1418636	Soil	0.9	39.3	11.2	66	0.1	30.4	10.9	479	2.47	10.3	1.3	3.0	4.3	66	0.3	1.0	0.2	49	1.44	0.070
1418639	Soil	0.9	16.1	22.1	102	<0.1	12.3	15.5	852	4.49	3.8	1.0	2.0	15.9	23	0.2	0.2	0.2	66	0.53	0.136
1418645	Soil	0.2	13.9	24.2	145	<0.1	10.8	13.6	1995	4.09	2.1	1.3	6.1	18.9	47	0.4	0.3	0.2	42	1.28	0.110
1418642	Soil	0.3	16.5	12.5	85	<0.1	8.6	10.1	479	3.51	2.7	1.0	13.7	18.6	24	<0.1	0.3	0.1	34	0.40	0.086
1418643	Soil	0.9	15.0	11.1	79	<0.1	14.1	11.2	461	3.35	11.9	1.0	19.5	10.9	26	0.1	0.4	0.2	52	0.37	0.038
1418628	Soil	0.9	22.4	45.6	114	<0.1	12.1	10.2	622	3.48	4.8	1.6	14.9	13.9	35	<0.1	0.3	0.5	45	0.52	0.107
1418646	Soil	0.8	21.0	20.8	119	<0.1	10.9	17.0	867	5.11	3.0	2.0	4.5	26.5	28	0.1	0.5	0.2	59	0.48	0.107
1418647	Soil	1.0	28.8	79.2	107	0.1	15.1	13.7	694	4.28	4.6	1.9	7.3	21.7	24	0.2	0.5	1.0	65	0.30	0.057

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 8 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	TI	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.01	0.1	0.01	0.05	1	0.5	0.2	
1418633	Soil	17	26	0.50	374	0.058	2	1.18	0.021	0.05	0.2	0.05	3.8	<0.1	<0.05	4	0.7	<0.2
1418620	Soil	42	25	0.39	304	0.024	2	1.47	0.007	0.11	0.8	0.04	6.2	<0.1	<0.05	5	<0.5	<0.2
1418623	Soil	60	18	1.00	379	0.137	3	2.14	0.015	0.95	0.1	0.02	5.8	0.5	<0.05	9	<0.5	<0.2
1335991	Soil	61	22	1.23	359	0.208	1	2.39	0.010	1.05	<0.1	<0.01	7.0	0.6	<0.05	11	<0.5	<0.2
1418625	Soil	24	23	0.60	252	0.054	3	1.22	0.023	0.15	0.3	0.04	5.0	<0.1	<0.05	4	<0.5	<0.2
1418618	Soil	30	21	1.01	252	0.114	1	2.29	0.009	0.65	0.2	<0.01	4.1	0.3	<0.05	10	<0.5	<0.2
1418616	Soil	50	25	0.92	201	0.060	1	1.85	0.014	0.30	0.4	0.01	5.1	0.2	<0.05	9	<0.5	<0.2
1418708	Soil	24	29	0.63	359	0.094	3	1.37	0.027	0.19	0.2	0.03	4.6	0.1	<0.05	5	<0.5	<0.2
1418621	Soil	39	31	0.92	270	0.151	2	2.07	0.011	0.61	0.1	0.01	5.8	0.4	<0.05	8	<0.5	<0.2
1418619	Soil	54	26	0.97	285	0.128	1	2.43	0.011	0.77	0.1	0.02	8.6	0.4	<0.05	10	<0.5	<0.2
1418617	Soil	27	33	0.63	324	0.092	3	1.62	0.018	0.13	0.2	0.05	4.9	0.1	<0.05	6	<0.5	<0.2
1418615	Soil	25	27	0.66	232	0.130	2	1.75	0.014	0.36	0.2	0.02	3.9	0.2	<0.05	8	<0.5	<0.2
1418626	Soil	37	24	0.74	187	0.065	<1	1.56	0.016	0.19	0.2	0.03	6.2	0.2	<0.05	6	<0.5	0.4
1418632	Soil	19	25	0.52	315	0.060	1	1.23	0.022	0.06	0.2	0.03	4.0	<0.1	<0.05	4	<0.5	<0.2
1418638	Soil	87	15	1.06	278	0.149	<1	2.40	0.008	0.97	<0.1	<0.01	4.0	0.4	<0.05	10	<0.5	<0.2
1418634	Soil	19	27	0.59	360	0.066	2	1.29	0.024	0.07	0.2	0.03	4.5	<0.1	<0.05	4	<0.5	<0.2
1418631	Soil	30	29	0.55	275	0.081	2	1.54	0.019	0.09	0.3	0.05	4.8	<0.1	<0.05	5	0.9	<0.2
1418627	Soil	29	18	0.46	231	0.035	<1	1.43	0.010	0.19	0.2	0.02	4.2	0.1	<0.05	6	<0.5	<0.2
1418637	Soil	17	25	0.63	353	0.061	3	1.17	0.022	0.07	0.2	0.05	4.1	<0.1	<0.05	3	0.5	<0.2
1418640	Soil	48	21	0.83	338	0.102	1	2.08	0.009	0.68	<0.1	0.02	7.8	0.3	<0.05	10	<0.5	<0.2
1418629	Soil	35	18	0.64	194	0.095	<1	1.63	0.014	0.31	0.2	0.01	4.8	0.2	<0.05	7	<0.5	<0.2
1418630	Soil	32	20	0.67	158	0.080	<1	1.55	0.018	0.24	0.2	0.02	5.7	0.2	<0.05	7	<0.5	<0.2
1418636	Soil	16	27	0.67	424	0.058	2	1.19	0.026	0.06	0.2	0.05	4.1	<0.1	<0.05	3	0.8	<0.2
1418639	Soil	32	21	1.10	310	0.199	<1	2.50	0.009	1.06	0.1	<0.01	7.3	0.4	<0.05	11	<0.5	<0.2
1418645	Soil	71	17	0.99	306	0.098	<1	2.07	0.008	0.65	<0.1	0.02	7.7	0.4	<0.05	10	<0.5	<0.2
1418642	Soil	43	12	0.67	225	0.044	<1	1.84	0.009	0.54	0.3	0.03	5.1	0.3	<0.05	6	<0.5	<0.2
1418643	Soil	37	22	0.70	234	0.084	<1	1.91	0.009	0.52	0.1	0.02	5.1	0.3	<0.05	7	<0.5	<0.2
1418628	Soil	34	18	0.63	309	0.062	<1	1.77	0.010	0.39	0.2	<0.01	5.1	0.2	<0.05	8	0.8	<0.2
1418646	Soil	95	16	1.26	280	0.201	<1	2.72	0.011	1.25	0.1	<0.01	4.4	0.8	<0.05	12	<0.5	<0.2
1418647	Soil	58	19	0.96	271	0.129	<1	2.15	0.009	0.93	0.1	0.01	6.5	0.5	<0.05	10	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 9 of 9

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
Unit		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%
MDL		0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001
1418648	Soil	0.8	13.3	13.1	58	<0.1	10.6	8.6	436	2.73	5.6	0.6	2.7	5.8	13	<0.1	0.3	0.2	51	0.20	0.076
1418641	Soil	0.5	22.4	20.8	79	<0.1	13.6	11.5	513	3.46	9.7	1.2	13.3	13.1	34	0.1	0.4	0.2	45	0.58	0.120
1418644	Soil	1.9	18.2	34.2	63	0.1	24.5	11.2	516	2.98	32.4	1.3	18.6	8.5	26	0.2	0.5	0.5	51	0.37	0.043



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 9 of 9

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1418648	Soil	16	21	0.56	122	0.080	<1	1.60	0.008	0.18	0.2	0.01	4.3	0.1	<0.05	6	<0.5	<0.2
1418641	Soil	40	19	0.58	363	0.032	<1	1.93	0.010	0.37	0.2	0.02	7.1	0.2	<0.05	6	<0.5	<0.2
1418644	Soil	24	43	0.44	270	0.060	<1	1.59	0.009	0.22	0.2	0.01	6.1	0.1	<0.05	5	<0.5	0.3



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 1 of 2 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000209.1

Method	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
Analyte	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	
Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%	
MDL	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001	
Pulp Duplicates																					
1390481	Soil	0.7	27.4	8.7	83	0.1	25.9	9.1	425	2.26	8.6	0.6	3.9	3.7	45	0.5	0.8	0.1	39	1.47	0.079
REP 1390481	QC	0.6	27.9	8.8	83	0.1	26.8	9.3	430	2.29	9.2	0.6	1.7	3.6	45	0.4	0.9	0.1	39	1.48	0.082
1418721	Soil	1.5	19.3	10.6	94	<0.1	12.0	11.2	637	4.06	5.0	1.5	1.2	21.4	17	<0.1	0.4	0.3	57	0.31	0.090
REP 1418721	QC	1.3	18.7	10.7	95	<0.1	12.7	11.6	636	4.05	4.7	1.5	1.6	20.8	18	<0.1	0.4	0.2	58	0.30	0.084
1335971	Soil	0.8	18.6	8.8	55	<0.1	20.0	9.5	250	2.75	9.8	0.8	15.8	5.9	19	<0.1	0.5	0.2	54	0.21	0.041
REP 1335971	QC	0.8	18.0	8.9	52	<0.1	20.2	9.2	248	2.71	9.1	0.8	15.0	6.0	18	<0.1	0.6	0.1	54	0.21	0.040
1390490	Soil	1.2	31.7	19.4	72	0.2	22.4	9.1	544	2.51	8.3	2.0	7.4	6.2	57	0.3	0.5	0.4	48	0.96	0.080
REP 1390490	QC	1.2	30.9	19.8	72	0.2	21.8	9.0	547	2.51	8.7	2.0	8.8	6.3	58	0.3	0.6	0.4	49	0.96	0.077
1418613	Soil	1.5	18.0	15.8	60	0.1	19.2	8.8	411	2.35	7.0	1.5	6.6	6.1	39	0.2	0.4	0.3	50	0.53	0.080
REP 1418613	QC	1.5	18.9	15.7	63	0.1	19.3	9.0	419	2.39	7.3	1.6	5.9	6.0	40	0.2	0.4	0.2	51	0.54	0.080
1418634	Soil	1.0	30.1	11.3	65	0.1	26.0	10.6	442	2.50	8.9	1.0	3.9	5.3	47	0.4	0.8	0.2	49	0.83	0.070
REP 1418634	QC	0.9	31.1	11.3	67	0.1	27.3	10.9	450	2.53	9.1	1.0	3.1	5.2	49	0.4	0.8	0.2	49	0.83	0.071
Reference Materials																					
STD DS10	Standard	14.8	145.2	143.3	347	1.8	73.2	13.0	870	2.80	43.3	2.7	74.9	7.5	63	2.2	8.5	10.5	43	1.09	0.077
STD DS10	Standard	14.9	151.9	149.5	357	1.8	76.4	12.8	882	2.80	45.2	2.6	70.2	7.3	62	2.0	8.1	10.4	42	1.07	0.074
STD DS10	Standard	15.3	159.9	147.7	373	1.8	76.0	13.5	901	2.90	47.1	2.6	79.3	7.3	64	2.4	8.3	11.1	46	1.11	0.076
STD DS10	Standard	14.9	153.0	149.2	364	1.8	74.4	12.6	882	2.82	46.0	2.8	77.5	7.8	73	2.8	9.8	13.5	44	1.06	0.078
STD DS10	Standard	14.2	150.1	144.4	359	1.8	71.9	12.5	850	2.69	44.0	2.7	86.6	7.6	70	2.7	9.5	12.7	43	1.04	0.072
STD DS10	Standard	15.4	156.6	153.1	367	1.8	79.4	13.1	897	2.90	46.3	3.0	79.0	8.1	71	2.5	9.9	13.4	45	1.10	0.076
STD OXC129	Standard	1.1	25.9	5.8	39	<0.1	74.4	19.9	416	3.01	0.8	0.7	191.0	1.6	182	<0.1	<0.1	<0.1	50	0.75	0.097
STD OXC129	Standard	1.1	26.4	6.3	40	<0.1	79.1	20.5	416	3.03	0.9	0.7	197.8	1.7	162	<0.1	<0.1	<0.1	49	0.68	0.099
STD OXC129	Standard	1.3	26.8	6.2	40	<0.1	76.5	20.6	422	3.06	<0.5	0.7	205.9	1.8	165	<0.1	<0.1	<0.1	54	0.66	0.103
STD OXC129	Standard	1.2	27.5	6.7	44	<0.1	77.1	20.3	421	3.12	0.6	0.7	194.0	2.0	196	<0.1	<0.1	<0.1	53	0.68	0.101
STD OXC129	Standard	1.2	27.3	6.5	41	<0.1	75.6	19.7	403	2.94	<0.5	0.7	203.1	1.9	185	<0.1	<0.1	<0.1	50	0.57	0.096
STD OXC129	Standard	1.3	27.0	6.7	43	<0.1	79.7	20.2	420	3.12	<0.5	0.7	204.0	2.0	196	0.2	<0.1	<0.1	54	0.69	0.102
STD DS10 Expected		15.1	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	2.59	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	0.0765
STD OXC129 Expected		1.3	28	6.3	42.9		79.5	20.3	421	3.065	0.6	0.72	195	1.9					51	0.665	0.102
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001



QUALITY CONTROL REPORT

WHI16000209.1

Method	Analyte	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																		
1390481	Soil	14	23	0.71	394	0.054	2	1.04	0.022	0.05	0.2	0.03	3.4	<0.1	<0.05	3	0.6	<0.2
REP 1390481	QC	14	23	0.72	412	0.057	2	1.05	0.022	0.05	0.2	0.03	3.5	<0.1	<0.05	3	<0.5	<0.2
1418721	Soil	29	20	0.94	209	0.100	<1	2.06	0.010	0.52	0.1	0.02	5.3	0.3	<0.05	10	<0.5	<0.2
REP 1418721	QC	29	19	0.94	196	0.103	<1	2.09	0.010	0.54	<0.1	0.01	5.1	0.3	<0.05	11	<0.5	<0.2
1335971	Soil	16	32	0.51	193	0.083	1	1.42	0.011	0.14	0.2	0.03	4.9	0.2	<0.05	5	<0.5	<0.2
REP 1335971	QC	16	33	0.51	191	0.083	<1	1.41	0.010	0.14	0.1	0.02	4.6	<0.1	<0.05	5	<0.5	<0.2
1390490	Soil	22	25	0.50	302	0.065	2	1.23	0.023	0.13	0.2	0.03	4.5	<0.1	<0.05	4	<0.5	<0.2
REP 1390490	QC	23	25	0.50	306	0.063	2	1.25	0.023	0.13	0.3	0.05	4.3	<0.1	<0.05	4	<0.5	<0.2
1418613	Soil	23	31	0.46	266	0.074	2	1.38	0.018	0.06	0.3	0.05	4.5	<0.1	<0.05	4	0.7	<0.2
REP 1418613	QC	23	31	0.47	271	0.075	2	1.38	0.018	0.05	0.3	0.03	4.6	<0.1	<0.05	5	<0.5	<0.2
1418634	Soil	19	27	0.59	360	0.066	2	1.29	0.024	0.07	0.2	0.03	4.5	<0.1	<0.05	4	<0.5	<0.2
REP 1418634	QC	20	26	0.59	369	0.064	3	1.29	0.024	0.07	0.2	0.04	4.6	<0.1	<0.05	4	<0.5	<0.2
Reference Materials																		
STD DS10	Standard	19	55	0.79	376	0.090	6	1.15	0.077	0.36	3.2	0.27	3.3	4.9	0.26	5	2.6	5.0
STD DS10	Standard	17	55	0.78	352	0.085	8	1.09	0.074	0.35	3.2	0.27	3.1	5.1	0.27	5	2.1	4.8
STD DS10	Standard	18	59	0.79	347	0.082	7	1.08	0.074	0.34	3.5	0.28	3.2	5.2	0.29	4	2.6	4.7
STD DS10	Standard	19	55	0.80	351	0.081	8	1.07	0.071	0.33	3.2	0.29	3.0	5.1	0.28	4	2.6	4.7
STD DS10	Standard	18	54	0.77	344	0.077	7	1.03	0.072	0.33	3.1	0.29	3.0	5.0	0.28	4	2.5	4.8
STD DS10	Standard	19	57	0.82	370	0.084	8	1.07	0.070	0.34	3.5	0.27	3.1	5.3	0.29	5	2.1	5.2
STD OXC129	Standard	12	50	1.52	49	0.396	<1	1.65	0.612	0.39	<0.1	<0.01	1.1	<0.1	<0.05	6	<0.5	<0.2
STD OXC129	Standard	12	50	1.52	47	0.395	<1	1.57	0.604	0.38	<0.1	<0.01	1.4	<0.1	<0.05	6	<0.5	<0.2
STD OXC129	Standard	12	52	1.54	48	0.406	1	1.55	0.587	0.36	<0.1	<0.01	1.1	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	13	51	1.52	50	0.403	2	1.57	0.588	0.37	<0.1	<0.01	0.7	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	13	49	1.46	47	0.368	2	1.49	0.584	0.39	<0.1	<0.01	0.9	<0.1	<0.05	5	<0.5	<0.2
STD OXC129	Standard	13	53	1.51	52	0.417	2	1.54	0.579	0.37	0.1	0.06	1.1	<0.1	<0.05	6	0.8	0.3
STD DS10 Expected		17.5	54.6	0.775	359	0.0817		1.0755	0.067	0.338	3.32	0.3	3	5.1	0.29	4.5	2.3	5.01
STD OXC129 Expected		13	52	1.545	50	0.4	1	1.58	0.6	0.37			1.1			5.6		
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000209.1

		AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	%
		0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2	0.01	0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001
BLK	Blank	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	<0.001



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 09, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000209.1

		AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201	AQ201
		La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		1	1	0.01	1	0.001	1	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<1	<1	<0.01	<1	<0.001	<1	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2

Appendix C: GT Probe Samples Assay Certificate



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 02, 2016
Report Date: August 12, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000140.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV-2016-07-26-Rock-GTP
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1
CANADA

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	134	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	134	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	134	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	134	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1335660	Rock	0.97	0.036	4.1	80.1	96.6	232	0.2	101.4	20.9	1687	4.00	43.7	32.3	6.4	40	0.7	1.5	0.4	94	0.39
1335661	Rock	1.33	0.013	2.6	66.7	12.6	131	0.1	69.6	14.8	922	3.22	31.9	7.7	7.9	49	0.7	1.7	0.2	83	0.89
1335662	Rock	1.11	0.043	1.6	28.2	10.7	51	<0.1	26.2	9.2	221	2.39	33.5	62.4	6.4	70	0.1	1.4	0.2	36	0.55
1335663	Rock	0.94	0.008	1.4	22.3	7.7	44	<0.1	27.8	8.6	220	2.36	34.7	6.7	5.8	47	0.2	1.4	0.2	39	0.25
1335664	Rock	1.27	0.008	0.7	21.4	8.0	46	<0.1	22.1	10.2	235	2.35	17.8	3.5	8.1	42	0.2	0.8	0.2	37	0.30
1335665	Rock	1.54	0.021	1.1	25.0	8.8	57	<0.1	25.3	9.0	283	2.45	24.2	3.2	8.9	46	0.4	1.0	0.3	39	0.31
1338651	Rock	0.85	0.060	9.7	50.9	17.9	117	0.6	102.8	16.9	513	4.42	54.1	50.1	2.2	24	0.3	1.0	0.2	73	0.10
1338652	Rock	1.28	0.146	11.6	138.1	20.6	109	0.6	90.4	14.6	655	4.06	49.3	139.6	1.9	29	0.4	0.5	0.3	69	0.09
1338653	Rock	0.92	0.211	10.1	35.4	174.8	75	0.9	78.5	11.0	373	2.85	80.5	241.4	1.1	50	0.2	0.9	1.0	69	0.79
1338654	Rock	1.23	0.051	8.9	144.8	5.7	110	<0.1	21.3	33.6	1755	7.25	22.6	59.8	1.0	22	0.1	1.4	<0.1	165	0.34
1338655	Rock	1.60	0.023	4.3	186.8	3.6	88	<0.1	21.8	28.3	1161	5.76	9.3	19.9	0.8	42	0.2	0.6	<0.1	150	0.65
1338656	Rock	1.45	0.010	0.9	27.1	9.9	52	<0.1	11.5	6.4	306	2.16	14.2	6.7	7.6	25	0.1	0.6	0.1	22	0.14
1338657	Rock	1.21	0.014	1.0	43.9	2.8	54	<0.1	71.6	25.0	713	3.85	15.4	10.2	3.8	39	0.1	0.3	<0.1	80	0.71
1338658	Rock	1.20	0.069	1.2	52.4	5.9	65	0.1	59.9	29.6	947	4.55	23.3	61.9	6.3	65	<0.1	0.4	<0.1	95	0.66
1338659	Rock	1.27	0.049	1.4	21.0	9.0	44	0.3	13.4	6.5	344	2.13	20.0	39.3	3.0	35	<0.1	0.4	<0.1	29	0.14
1338660	Rock	1.16	0.028	2.3	47.4	21.2	69	0.2	45.2	22.7	993	4.09	56.5	30.1	5.9	56	0.1	2.4	0.1	77	0.26
1338661	Rock	1.79	0.008	1.2	10.4	14.8	18	<0.1	10.8	4.7	304	1.24	16.1	11.0	7.2	39	<0.1	0.4	0.2	17	0.10
1338662	Rock	1.09	0.078	1.4	42.4	12.8	69	0.2	57.1	23.2	858	4.25	40.8	83.5	6.6	73	0.2	1.4	<0.1	86	0.47
1338663	Rock	1.11	0.167	2.0	48.6	10.9	71	0.3	28.4	13.6	744	3.66	26.1	136.1	4.7	47	0.2	0.8	<0.1	70	0.31
1338664	Rock	1.16	<0.005	0.8	144.5	0.8	99	<0.1	21.5	33.6	1484	6.84	1.9	2.3	0.2	56	<0.1	0.1	<0.1	211	0.53
1338665	Rock	1.25	<0.005	0.2	137.2	5.7	52	<0.1	39.3	19.9	493	3.18	2.9	3.5	2.0	32	0.1	0.1	<0.1	103	0.70
1338666	Rock	1.50	<0.005	0.1	85.7	1.9	24	<0.1	16.3	7.6	218	1.34	0.8	<0.5	1.6	21	<0.1	<0.1	<0.1	47	0.89
1338667	Rock	1.70	0.010	0.2	94.0	2.0	82	<0.1	22.3	18.0	751	4.41	1.7	8.1	0.4	55	<0.1	<0.1	<0.1	129	0.65
1338668	Rock	1.24	<0.005	<0.1	30.5	2.7	50	<0.1	52.0	18.1	512	2.34	0.9	<0.5	1.0	37	<0.1	<0.1	<0.1	62	0.82
1338669	Rock	1.28	<0.005	0.2	98.7	1.5	45	<0.1	16.6	16.4	381	2.62	<0.5	<0.5	1.4	24	<0.1	<0.1	<0.1	84	0.73
1338670	Rock	1.10	<0.005	0.1	74.0	1.2	44	<0.1	23.3	18.8	533	2.89	0.8	<0.5	0.7	31	<0.1	<0.1	<0.1	87	0.72
1338671	Rock	0.91	<0.005	0.3	97.7	13.5	47	<0.1	21.3	15.3	633	3.03	0.7	0.7	0.9	36	<0.1	0.1	0.2	109	0.78
1338672	Rock	1.19	<0.005	0.3	34.8	8.9	133	<0.1	12.4	19.6	864	3.63	1.6	<0.5	0.4	29	0.2	0.2	0.1	101	0.71
1338673	Rock	1.82	<0.005	0.2	130.3	2.1	58	<0.1	13.8	15.3	442	2.80	1.7	1.2	0.3	30	0.1	0.1	0.3	95	1.11
1338674	Rock	1.76	0.006	<0.1	118.4	1.3	86	<0.1	8.0	25.6	558	4.99	1.8	4.8	0.4	45	<0.1	<0.1	<0.1	170	0.91



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1335660	Rock	0.094	20	79	0.91	821	0.054	<20	1.45	0.024	0.45	0.1	0.13	9.0	0.3	<0.05	6	<0.5	<0.2
1335661	Rock	0.077	19	70	0.83	1079	0.085	<20	1.48	0.030	0.63	0.1	0.10	8.8	0.4	<0.05	6	<0.5	<0.2
1335662	Rock	0.046	13	24	0.40	1307	0.044	<20	0.88	0.033	0.27	<0.1	0.06	4.5	0.2	<0.05	3	<0.5	<0.2
1335663	Rock	0.029	15	31	0.37	421	0.048	<20	0.95	0.047	0.24	<0.1	0.07	4.3	0.1	<0.05	3	<0.5	<0.2
1335664	Rock	0.045	17	23	0.40	470	0.049	<20	0.89	0.036	0.23	0.1	0.06	3.9	0.1	<0.05	3	<0.5	<0.2
1335665	Rock	0.054	18	27	0.40	1226	0.043	<20	0.95	0.041	0.29	0.1	0.07	4.3	0.1	<0.05	3	<0.5	<0.2
1338651	Rock	0.029	9	64	0.12	917	0.002	<20	0.53	0.031	0.20	0.2	0.21	16.1	0.2	<0.05	2	0.7	0.4
1338652	Rock	0.022	5	62	0.10	1247	0.002	<20	0.51	0.036	0.16	<0.1	0.26	12.3	0.2	<0.05	2	<0.5	0.7
1338653	Rock	0.014	4	63	0.18	2433	0.003	<20	0.73	0.007	0.20	0.2	0.37	8.5	0.2	0.06	2	<0.5	1.3
1338654	Rock	0.119	7	11	0.20	687	0.007	<20	0.96	0.015	0.41	0.2	0.36	23.8	0.7	<0.05	3	<0.5	<0.2
1338655	Rock	0.104	6	18	0.69	1060	0.041	<20	1.60	0.062	0.50	0.3	0.12	18.9	0.2	<0.05	7	<0.5	<0.2
1338656	Rock	0.035	16	18	0.32	1294	0.026	<20	0.93	0.020	0.52	0.5	0.08	5.6	0.2	<0.05	3	<0.5	<0.2
1338657	Rock	0.112	14	150	1.37	1297	0.081	<20	1.77	0.063	0.82	0.2	0.05	14.5	0.2	<0.05	6	<0.5	<0.2
1338658	Rock	0.140	26	121	1.49	2414	0.103	<20	1.88	0.039	0.93	0.6	0.07	17.8	0.3	<0.05	7	<0.5	<0.2
1338659	Rock	0.026	8	21	0.18	1041	0.008	<20	0.72	0.030	0.32	0.7	0.20	6.3	0.2	<0.05	2	<0.5	<0.2
1338660	Rock	0.067	13	52	0.25	1334	0.003	<20	0.75	0.012	0.33	0.4	0.20	14.1	0.4	<0.05	3	<0.5	<0.2
1338661	Rock	0.013	11	13	0.11	1047	<0.001	<20	0.56	0.004	0.26	0.3	0.15	2.6	<0.1	<0.05	1	<0.5	<0.2
1338662	Rock	0.082	18	93	0.82	2872	0.033	<20	1.42	0.024	0.65	0.7	0.19	16.0	0.4	0.06	5	<0.5	<0.2
1338663	Rock	0.031	12	40	0.50	2297	0.021	<20	1.27	0.030	0.48	0.5	0.24	13.2	0.3	0.05	4	<0.5	0.3
1338664	Rock	0.080	2	14	3.30	1097	0.374	<20	3.81	0.036	2.57	0.1	0.02	25.4	0.8	<0.05	13	<0.5	<0.2
1338665	Rock	0.051	7	201	1.85	215	0.199	<20	1.41	0.094	0.29	0.1	0.02	10.1	0.1	<0.05	6	<0.5	<0.2
1338666	Rock	0.070	6	74	0.76	229	0.144	<20	0.60	0.137	0.04	<0.1	<0.01	5.9	<0.1	<0.05	3	<0.5	<0.2
1338667	Rock	0.070	2	35	2.11	1107	0.364	<20	2.59	0.040	1.58	<0.1	0.07	6.5	0.3	<0.05	9	<0.5	<0.2
1338668	Rock	0.069	5	197	1.89	841	0.202	<20	1.58	0.086	0.71	<0.1	0.01	6.5	0.3	<0.05	6	<0.5	<0.2
1338669	Rock	0.058	6	54	1.49	354	0.218	<20	1.36	0.096	0.70	<0.1	0.01	6.6	0.3	<0.05	5	<0.5	<0.2
1338670	Rock	0.058	3	94	1.93	392	0.240	<20	1.81	0.102	0.79	<0.1	<0.01	7.6	0.1	<0.05	7	<0.5	<0.2
1338671	Rock	0.052	5	78	1.38	262	0.194	<20	1.37	0.106	0.46	<0.1	0.02	12.0	0.1	<0.05	6	<0.5	<0.2
1338672	Rock	0.055	2	91	1.76	423	0.233	<20	1.93	0.057	1.00	0.1	0.02	10.4	0.3	<0.05	7	<0.5	<0.2
1338673	Rock	0.054	2	91	1.34	157	0.174	<20	1.45	0.196	0.36	<0.1	<0.01	9.8	<0.1	<0.05	5	<0.5	<0.2
1338674	Rock	0.053	2	8	1.65	266	0.180	<20	2.14	0.121	0.55	<0.1	<0.01	18.1	0.1	<0.05	7	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1338675	Rock	0.97	0.019	0.5	55.1	1.8	79	<0.1	13.6	25.4	1140	5.78	13.8	14.1	1.5	45	0.1	0.4	<0.1	150	1.49
1338676	Rock	0.88	<0.005	0.7	39.0	2.2	58	<0.1	11.3	14.3	763	4.17	13.1	<0.5	8.4	39	<0.1	0.8	0.3	49	0.53
1338677	Rock	1.29	<0.005	1.1	10.4	1.6	57	<0.1	6.5	7.3	675	2.70	5.4	<0.5	8.8	26	<0.1	0.2	<0.1	24	0.37
1338678	Rock	0.85	<0.005	1.2	4.5	8.4	23	<0.1	5.2	4.7	699	1.43	7.4	<0.5	8.0	21	<0.1	0.2	0.4	16	0.20
1338679	Rock	1.03	<0.005	0.4	4.6	2.4	50	<0.1	8.9	8.2	631	2.43	1.6	1.7	7.7	34	<0.1	0.3	<0.1	48	0.44
1338680	Rock	1.04	<0.005	1.1	11.5	5.0	70	<0.1	17.1	9.1	1423	3.52	4.7	5.1	9.4	67	<0.1	0.8	0.3	76	0.31
1338681	Rock	1.83	<0.005	0.3	4.2	9.5	48	<0.1	12.8	7.1	664	2.41	1.3	2.7	11.8	22	<0.1	0.4	0.2	41	0.26
1338682	Rock	0.76	<0.005	0.4	5.3	1.7	35	<0.1	7.9	11.3	500	2.78	1.7	<0.5	4.7	34	<0.1	0.1	<0.1	76	0.52
1338683	Rock	1.66	<0.005	0.5	3.6	2.3	36	<0.1	8.7	5.8	521	1.96	2.0	1.0	9.4	33	<0.1	0.2	<0.1	48	0.29
1338684	Rock	1.27	<0.005	0.7	7.5	5.5	53	<0.1	13.4	6.8	733	2.45	3.9	<0.5	11.7	24	<0.1	0.3	0.2	43	0.24
1338685	Rock	0.80	<0.005	0.3	4.4	4.0	33	<0.1	9.7	5.8	449	2.19	1.3	2.2	11.4	17	<0.1	0.2	<0.1	40	0.24
1338686	Rock	1.26	<0.005	0.2	4.9	1.9	46	<0.1	6.3	7.2	607	2.28	0.7	<0.5	4.3	27	<0.1	<0.1	<0.1	40	0.39
1338687	Rock	1.25	<0.005	0.4	5.1	3.9	38	<0.1	6.4	8.7	712	2.79	1.5	<0.5	9.3	24	<0.1	0.2	<0.1	41	0.29
1338688	Rock	0.88	<0.005	0.5	4.7	6.0	39	<0.1	9.1	6.9	876	2.43	1.4	3.8	10.9	78	<0.1	0.2	<0.1	43	0.32
1338689	Rock	1.23	<0.005	0.8	2.9	2.1	37	<0.1	7.7	7.8	815	2.37	2.1	23.5	10.0	21	<0.1	0.3	0.2	34	0.22
1338690	Rock	1.35	0.009	0.7	4.7	4.1	39	<0.1	8.6	7.2	832	2.30	2.5	7.2	10.8	24	<0.1	0.4	0.2	44	0.29
1338691	Rock	1.19	0.029	1.2	5.4	5.0	41	<0.1	7.8	7.8	1156	2.81	6.9	18.9	8.3	36	<0.1	0.4	0.2	41	0.32
1338692	Rock	0.91	0.056	3.2	18.8	21.0	65	0.3	13.5	10.1	880	3.71	13.7	41.9	4.8	58	0.1	1.6	0.1	67	0.19
1338693	Rock	1.51	0.047	0.8	10.3	9.7	41	0.2	8.4	6.3	563	2.21	4.0	43.1	7.4	33	<0.1	0.7	0.1	36	0.34
1338694	Rock	1.04	0.063	2.2	20.6	8.0	87	0.4	7.3	9.5	983	2.99	15.4	70.9	4.3	72	0.3	2.8	0.1	63	0.28
1338695	Rock	1.19	0.017	0.9	13.9	6.7	54	0.2	7.5	7.9	750	2.83	1.9	20.4	5.4	69	0.3	0.3	0.2	60	1.19
1338696	Rock	0.68	0.012	2.5	68.2	3.6	97	<0.1	56.6	23.0	2364	4.81	4.7	11.5	1.3	55	0.1	1.2	<0.1	90	1.19
1338697	Rock	1.11	0.006	1.7	49.8	2.3	92	<0.1	26.4	26.3	1306	5.74	4.0	6.9	1.3	29	0.2	0.4	<0.1	146	0.34
1338698	Rock	0.96	0.025	3.4	90.9	5.8	107	<0.1	79.0	27.4	1757	5.38	29.3	23.1	2.0	38	0.2	1.8	<0.1	111	0.25
1338699	Rock	0.97	0.531	0.8	83.0	3.7	79	0.2	35.8	18.9	850	3.72	13.2	628.4	1.0	50	<0.1	0.4	<0.1	112	0.69
1338700	Rock	1.11	0.049	1.3	83.1	5.1	103	<0.1	55.1	24.7	1364	4.43	29.8	33.6	2.0	38	0.2	0.6	<0.1	143	0.31
1338701	Rock	1.17	0.012	1.0	103.6	3.6	103	<0.1	41.6	23.8	1026	4.71	18.7	10.2	0.7	36	0.2	0.7	<0.1	158	0.45
1338702	Rock	0.96	0.006	0.6	151.1	4.4	101	<0.1	24.6	24.3	948	4.96	19.4	8.2	1.0	50	0.1	0.4	<0.1	157	0.55
1338703	Rock	1.24	0.011	0.4	120.9	3.7	91	<0.1	24.4	21.9	833	3.96	8.0	13.6	1.1	39	<0.1	0.3	<0.1	115	0.63
1338704	Rock	0.69	<0.005	0.6	38.4	5.7	49	<0.1	21.4	7.7	419	2.27	15.5	0.8	8.3	67	0.1	0.4	<0.1	47	1.71



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
	MDL	%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1338675	Rock	0.079	9	11	1.25	449	0.061	<20	1.87	0.041	0.46	<0.1	0.03	22.1	0.1	<0.05	8	<0.5	<0.2	
1338676	Rock	0.058	31	44	0.77	517	0.142	<20	1.58	0.067	0.65	<0.1	0.09	9.3	0.2	<0.05	7	<0.5	0.2	
1338677	Rock	0.055	33	18	0.61	710	0.176	<20	1.36	0.049	0.81	0.2	0.01	5.5	0.3	<0.05	6	<0.5	<0.2	
1338678	Rock	0.045	7	7	0.17	429	0.002	<20	0.73	0.021	0.31	<0.1	0.02	7.1	<0.1	<0.05	3	<0.5	<0.2	
1338679	Rock	0.054	20	24	0.86	1211	0.186	<20	1.50	0.051	1.04	0.1	<0.01	5.3	0.3	<0.05	7	<0.5	<0.2	
1338680	Rock	0.095	30	33	0.78	3841	0.087	<20	1.79	0.034	0.88	<0.1	0.03	12.5	0.2	0.08	9	<0.5	<0.2	
1338681	Rock	0.059	34	27	0.84	642	0.163	<20	1.41	0.040	1.02	0.2	<0.01	5.6	0.3	<0.05	7	<0.5	<0.2	
1338682	Rock	0.069	15	19	1.37	806	0.202	<20	1.89	0.050	1.14	<0.1	0.01	7.5	0.3	<0.05	8	<0.5	<0.2	
1338683	Rock	0.067	22	22	0.79	965	0.105	<20	1.21	0.048	0.70	0.1	<0.01	7.5	0.1	<0.05	7	<0.5	<0.2	
1338684	Rock	0.052	39	24	0.74	483	0.103	<20	1.35	0.046	0.82	0.2	<0.01	6.2	0.2	<0.05	8	<0.5	<0.2	
1338685	Rock	0.053	40	24	0.86	376	0.112	<20	1.41	0.025	0.91	<0.1	<0.01	5.0	0.3	<0.05	7	<0.5	<0.2	
1338686	Rock	0.056	10	23	1.13	528	0.205	<20	1.60	0.054	1.04	0.1	<0.01	5.5	0.3	<0.05	7	<0.5	<0.2	
1338687	Rock	0.067	28	17	1.04	1198	0.141	<20	1.68	0.026	1.00	0.1	<0.01	7.8	0.3	<0.05	8	<0.5	<0.2	
1338688	Rock	0.058	16	25	1.01	2067	0.099	<20	1.64	0.032	1.04	0.1	0.01	7.0	0.4	<0.05	7	<0.5	<0.2	
1338689	Rock	0.047	21	21	0.59	936	0.084	<20	1.14	0.030	0.74	0.2	0.02	6.6	0.3	<0.05	5	<0.5	<0.2	
1338690	Rock	0.055	27	22	0.56	786	0.095	<20	1.10	0.057	0.66	0.2	0.05	10.5	0.2	<0.05	5	<0.5	<0.2	
1338691	Rock	0.040	13	15	0.38	873	0.033	<20	0.99	0.027	0.50	0.2	0.22	10.6	0.2	<0.05	4	<0.5	<0.2	
1338692	Rock	0.021	14	17	0.16	2116	0.008	<20	1.00	0.009	0.21	0.2	0.52	13.2	0.1	<0.05	3	<0.5	<0.2	
1338693	Rock	0.035	14	13	0.35	767	0.035	<20	0.81	0.019	0.38	0.2	0.19	7.3	0.1	<0.05	3	<0.5	<0.2	
1338694	Rock	0.017	11	13	0.09	2710	0.002	<20	0.69	0.004	0.10	<0.1	0.74	13.1	<0.1	0.06	2	<0.5	0.4	
1338695	Rock	0.034	14	16	0.37	1372	0.031	<20	0.74	0.037	0.43	0.1	0.10	12.9	0.1	<0.05	3	<0.5	<0.2	
1338696	Rock	0.092	8	68	0.80	891	0.053	<20	1.53	0.046	0.74	0.2	0.14	20.4	0.2	<0.05	6	<0.5	<0.2	
1338697	Rock	0.062	9	67	1.70	712	0.151	<20	2.27	0.029	1.57	<0.1	0.12	25.0	0.4	<0.05	8	<0.5	<0.2	
1338698	Rock	0.073	8	93	0.59	1331	0.022	<20	1.22	0.027	0.70	<0.1	0.48	21.8	0.2	<0.05	4	<0.5	<0.2	
1338699	Rock	0.047	5	69	1.05	1106	0.090	<20	1.52	0.083	0.53	0.6	0.19	17.7	0.2	<0.05	5	<0.5	0.8	
1338700	Rock	0.053	7	133	0.70	3741	0.029	<20	1.29	0.054	0.64	0.1	0.21	24.0	0.2	0.08	6	<0.5	<0.2	
1338701	Rock	0.055	4	61	1.07	1344	0.077	<20	1.54	0.061	0.74	0.1	0.13	25.6	0.2	<0.05	6	<0.5	<0.2	
1338702	Rock	0.069	6	41	1.41	2150	0.138	<20	2.28	0.067	1.07	0.2	0.10	18.5	0.3	<0.05	8	<0.5	<0.2	
1338703	Rock	0.066	4	37	1.59	644	0.169	<20	2.23	0.051	1.04	0.1	0.13	11.6	0.2	<0.05	6	<0.5	<0.2	
1338704	Rock	0.045	27	28	0.76	671	0.118	<20	1.16	0.060	0.47	0.2	0.08	5.7	0.2	<0.05	5	<0.5	<0.2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1338705	Rock	1.38	<0.005	0.5	49.7	6.5	85	<0.1	51.0	28.9	1071	5.03	18.9	2.5	9.6	54	0.1	0.6	<0.1	138	0.58
1338706	Rock	1.24	0.007	1.7	49.7	13.5	79	<0.1	19.7	13.5	904	3.86	52.7	10.4	7.0	39	0.2	0.7	<0.1	89	0.32
1338707	Rock	1.23	<0.005	0.4	51.1	7.4	72	<0.1	21.5	10.5	800	3.31	14.7	<0.5	5.3	54	0.1	0.4	<0.1	76	0.61
1338708	Rock	0.98	<0.005	0.3	31.4	10.8	68	<0.1	9.3	6.4	432	2.34	11.2	<0.5	8.6	40	<0.1	0.3	0.2	33	0.48
1338709	Rock	1.10	0.006	1.6	94.2	8.6	57	<0.1	12.5	10.9	616	2.99	28.0	3.3	2.7	46	<0.1	0.7	<0.1	96	0.57
1338710	Rock	1.20	<0.005	0.2	9.7	9.9	40	<0.1	3.4	3.1	262	1.24	12.3	<0.5	6.5	18	<0.1	0.3	0.1	14	0.12
1338711	Rock	1.67	<0.005	0.3	72.7	5.4	78	<0.1	11.8	14.1	584	3.32	14.7	<0.5	2.6	40	0.1	0.3	<0.1	97	0.59
1338712	Rock	0.96	<0.005	0.2	55.2	5.4	89	<0.1	40.1	13.7	533	3.44	3.6	<0.5	7.3	50	<0.1	0.2	<0.1	90	0.29
1338713	Rock	1.02	<0.005	0.3	22.5	5.5	53	<0.1	11.9	6.5	300	2.13	3.0	<0.5	4.1	29	<0.1	0.1	<0.1	30	0.31
1338714	Rock	0.91	0.008	<0.1	162.2	1.3	76	<0.1	18.9	23.0	741	4.35	3.0	1.9	0.6	58	<0.1	0.1	<0.1	191	1.48
1338715	Rock	0.96	1.359	0.3	314.2	6.5	58	2.9	10.8	9.2	498	2.58	6.3	4597.0	5.7	21	<0.1	0.2	0.1	69	0.30
1338716	Rock	1.09	0.031	<0.1	80.0	2.5	81	0.1	10.1	13.7	506	3.60	3.2	25.2	1.5	31	<0.1	0.1	<0.1	119	0.54
1338717	Rock	1.07	0.018	0.2	39.6	8.6	82	<0.1	7.2	8.3	550	2.69	10.6	11.0	6.5	28	0.2	1.2	<0.1	39	0.20
1338718	Rock	0.50	0.011	0.6	41.9	7.9	53	<0.1	32.5	11.6	383	2.68	14.4	6.8	4.3	37	<0.1	0.6	0.1	64	0.50
1338719	Rock	0.98	0.013	0.3	67.1	7.7	74	<0.1	32.0	12.7	616	3.21	20.7	10.8	6.2	37	<0.1	0.4	<0.1	70	0.54
1338720	Rock	0.83	<0.005	0.3	49.1	8.4	72	<0.1	55.8	30.4	1048	5.03	2.9	1.9	10.3	89	0.1	0.3	0.1	141	2.36
1338721	Rock	1.01	<0.005	0.4	41.9	5.7	64	<0.1	108.9	30.4	849	4.23	2.2	2.1	3.7	62	<0.1	2.2	<0.1	96	4.86
1338722	Rock	1.11	<0.005	0.3	253.1	1.0	64	<0.1	15.7	22.2	829	3.78	2.2	1.5	0.3	40	0.1	0.5	<0.1	143	1.29
1338723	Rock	1.34	0.006	0.1	206.0	1.0	88	<0.1	19.3	24.1	920	4.79	3.4	3.0	0.6	38	<0.1	0.2	<0.1	203	1.19
1338724	Rock	1.43	0.005	<0.1	151.5	0.8	76	<0.1	26.3	22.3	623	3.74	3.8	1.7	0.4	44	<0.1	0.1	<0.1	155	1.05
1338725	Rock	1.82	<0.005	<0.1	120.6	2.4	79	<0.1	18.7	19.4	516	3.56	3.0	3.8	0.3	51	<0.1	0.1	<0.1	121	1.20
1338726	Rock	1.19	<0.005	0.1	130.9	2.1	75	<0.1	24.1	18.4	719	4.04	7.4	1.4	0.9	45	<0.1	0.2	<0.1	142	1.10
1338727	Rock	1.06	<0.005	0.1	28.8	0.8	46	<0.1	100.1	29.4	499	3.90	3.7	1.7	0.5	30	<0.1	0.1	<0.1	106	0.69
1338728	Rock	0.99	<0.005	<0.1	57.1	0.6	40	<0.1	22.5	18.0	517	2.87	1.4	<0.5	0.1	33	<0.1	0.1	<0.1	100	1.52
1338729	Rock	1.32	<0.005	0.2	13.9	6.3	37	<0.1	5.6	3.3	208	1.07	1.8	1.5	4.0	75	0.1	0.2	<0.1	20	1.67
1338730	Rock	1.20	0.006	0.4	185.9	2.3	91	<0.1	15.0	21.2	980	4.96	3.4	4.7	0.6	82	0.2	0.5	<0.1	198	0.77
1338731	Rock	1.65	0.012	0.6	123.2	4.2	85	<0.1	64.9	23.9	1709	4.62	10.7	6.7	0.7	82	0.1	0.9	<0.1	166	0.52
1338732	Rock	1.06	0.017	0.6	150.0	2.4	98	<0.1	91.0	28.0	1360	5.35	8.0	7.5	0.9	41	0.1	1.5	<0.1	137	0.33
1338733	Rock	1.68	0.029	0.2	88.4	1.3	65	<0.1	20.9	21.2	972	4.01	1.1	4.6	0.8	35	<0.1	0.1	<0.1	130	0.75
1338734	Rock	1.16	0.006	0.1	91.6	1.4	37	<0.1	127.2	22.5	532	2.50	2.2	2.8	1.1	50	<0.1	0.1	<0.1	60	0.77



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1338705	Rock	0.156	34	117	1.77	3798	0.164	<20	2.08	0.027	1.40	0.1	0.11	19.2	0.3	0.07	8	<0.5	<0.2
1338706	Rock	0.049	18	29	0.57	2230	0.044	<20	1.34	0.021	0.69	0.1	0.36	14.1	0.3	<0.05	6	<0.5	<0.2
1338707	Rock	0.070	18	32	1.09	1610	0.141	<20	1.77	0.050	0.88	0.2	0.15	8.6	0.4	<0.05	6	<0.5	<0.2
1338708	Rock	0.034	25	18	0.66	2257	0.106	<20	1.45	0.027	0.83	0.2	0.16	6.9	0.5	<0.05	6	<0.5	<0.2
1338709	Rock	0.072	10	23	0.47	2087	0.055	<20	1.06	0.064	0.39	2.4	0.15	9.9	0.2	<0.05	5	<0.5	<0.2
1338710	Rock	0.016	22	8	0.27	1686	0.013	<20	0.89	0.032	0.35	0.1	0.14	4.8	0.2	<0.05	3	<0.5	<0.2
1338711	Rock	0.050	11	15	0.91	1743	0.138	<20	1.55	0.051	0.90	0.1	0.08	9.4	0.4	<0.05	6	<0.5	<0.2
1338712	Rock	0.048	22	61	1.22	917	0.196	<20	1.75	0.029	1.05	0.2	0.02	7.4	0.4	<0.05	8	<0.5	<0.2
1338713	Rock	0.028	18	18	0.72	469	0.117	<20	1.35	0.042	0.62	0.1	0.01	3.8	0.3	<0.05	5	<0.5	<0.2
1338714	Rock	0.087	6	14	1.59	544	0.221	<20	2.23	0.233	0.84	<0.1	0.03	12.9	0.2	<0.05	8	<0.5	<0.2
1338715	Rock	0.033	21	12	0.67	347	0.080	<20	1.32	0.060	0.63	0.2	0.33	7.3	0.3	<0.05	5	<0.5	2.9
1338716	Rock	0.055	7	14	1.13	1420	0.206	<20	1.95	0.075	1.20	<0.1	0.19	7.3	0.4	<0.05	7	<0.5	<0.2
1338717	Rock	0.051	16	19	0.57	1988	0.073	<20	1.20	0.033	0.73	0.2	1.03	7.7	0.4	<0.05	4	<0.5	<0.2
1338718	Rock	0.034	19	34	0.65	325	0.095	<20	1.42	0.066	0.21	0.2	0.10	6.3	0.2	<0.05	4	<0.5	<0.2
1338719	Rock	0.053	19	41	1.33	1371	0.149	<20	2.07	0.058	0.84	0.2	0.32	7.3	0.4	<0.05	7	<0.5	<0.2
1338720	Rock	0.158	39	144	2.07	2712	0.250	<20	2.50	0.045	1.46	<0.1	0.06	19.8	0.4	<0.05	9	<0.5	<0.2
1338721	Rock	0.066	15	161	1.60	2669	0.076	<20	2.02	0.033	1.05	<0.1	0.08	17.0	0.3	<0.05	6	<0.5	<0.2
1338722	Rock	0.095	3	9	0.98	409	0.156	<20	1.61	0.178	0.58	<0.1	0.05	11.4	0.1	<0.05	5	<0.5	<0.2
1338723	Rock	0.099	3	13	1.28	691	0.161	<20	2.27	0.147	0.63	<0.1	0.10	16.7	0.2	<0.05	9	<0.5	<0.2
1338724	Rock	0.078	3	32	1.39	395	0.173	<20	2.01	0.162	0.68	0.2	0.04	11.1	0.1	<0.05	7	<0.5	<0.2
1338725	Rock	0.059	2	23	1.30	339	0.203	<20	2.18	0.140	0.70	<0.1	0.04	8.4	0.2	<0.05	6	<0.5	<0.2
1338726	Rock	0.056	4	40	1.48	429	0.202	<20	2.33	0.156	0.89	1.0	0.07	13.1	0.3	<0.05	7	<0.5	<0.2
1338727	Rock	0.037	2	353	3.20	331	0.113	<20	3.05	0.053	0.53	<0.1	0.02	14.0	0.2	<0.05	8	<0.5	<0.2
1338728	Rock	0.045	<1	35	1.34	814	0.130	<20	1.65	0.284	0.21	<0.1	<0.01	13.0	<0.1	<0.05	6	<0.5	<0.2
1338729	Rock	0.021	16	12	0.35	410	0.037	<20	0.64	0.040	0.23	0.2	0.01	2.8	0.1	<0.05	3	<0.5	<0.2
1338730	Rock	0.105	5	16	1.13	4117	0.161	<20	1.79	0.077	0.74	0.2	0.02	15.2	0.2	0.09	8	<0.5	<0.2
1338731	Rock	0.065	6	113	1.36	3761	0.105	<20	1.86	0.047	0.94	2.5	0.06	19.7	0.3	0.08	8	<0.5	<0.2
1338732	Rock	0.064	6	149	1.03	1424	0.064	<20	1.62	0.033	0.90	0.2	0.22	23.0	0.3	<0.05	7	<0.5	<0.2
1338733	Rock	0.061	4	71	1.99	584	0.187	<20	2.14	0.092	0.93	<0.1	0.05	16.6	0.3	<0.05	8	<0.5	<0.2
1338734	Rock	0.042	6	330	1.78	1845	0.082	<20	1.54	0.089	0.42	<0.1	0.12	9.3	0.2	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1338735	Rock	1.26	0.006	0.2	53.7	18.1	51	<0.1	81.3	17.9	765	2.95	188.0	4.9	1.1	92	0.1	5.0	<0.1	88	1.33
1338736	Rock	1.41	0.006	0.1	74.6	0.9	68	<0.1	21.8	20.0	615	4.26	15.3	0.5	0.6	33	<0.1	0.2	<0.1	113	0.60
1338737	Rock	1.44	0.008	0.5	58.6	5.7	79	<0.1	47.8	23.7	1316	4.95	164.0	4.0	1.3	61	<0.1	6.1	<0.1	136	1.20
1338738	Rock	1.36	<0.005	0.8	77.4	6.8	98	<0.1	14.1	16.5	783	4.65	127.9	<0.5	0.6	49	0.2	12.8	<0.1	129	0.13
1338739	Rock	0.97	<0.005	0.7	59.2	11.1	75	<0.1	16.9	12.4	858	4.10	121.6	2.1	0.5	136	0.2	12.0	<0.1	130	0.44
1338740	Rock	0.97	<0.005	0.8	7.2	2.9	143	<0.1	8.3	23.9	931	5.28	14.7	1.7	2.0	41	<0.1	1.6	<0.1	107	0.49
1338741	Rock	1.18	0.007	0.7	19.7	3.0	84	<0.1	11.3	18.5	880	4.35	17.1	5.6	1.5	36	0.1	1.6	<0.1	110	0.47
1338742	Rock	1.31	0.009	0.4	115.5	1.3	58	<0.1	5.3	17.2	712	4.15	2.4	10.3	0.7	32	0.1	0.3	<0.1	139	0.84
1338743	Rock	1.09	0.029	1.8	26.7	10.6	74	0.2	9.5	17.6	1570	4.11	23.9	14.6	2.9	61	0.4	1.1	0.4	83	0.21
1338744	Rock	1.06	1.802	1.0	33.8	10.2	36	0.3	7.1	5.6	429	1.71	18.9	629.5	4.4	31	0.1	1.6	0.1	36	0.10
1338745	Rock	0.87	0.267	3.3	16.4	7.4	75	0.1	5.8	8.5	1041	3.24	8.2	130.8	1.7	56	0.2	1.8	0.4	31	0.20
1345926	Rock	1.29	<0.005	0.7	20.3	6.9	69	<0.1	24.1	14.9	393	2.67	1.8	4.9	22.8	13	<0.1	0.2	<0.1	19	0.28
1345927	Rock	0.97	<0.005	0.3	16.5	6.6	17	<0.1	8.9	6.2	346	1.36	6.2	3.7	10.4	63	<0.1	0.4	<0.1	11	3.19
1345928	Rock	1.23	<0.005	2.2	17.7	16.2	27	<0.1	16.4	7.4	692	2.72	146.4	4.0	17.0	14	<0.1	0.9	0.2	22	0.21
1345929	Rock	0.70	<0.005	0.2	15.4	21.7	52	<0.1	14.3	7.2	427	1.98	4.0	1.7	14.0	30	0.1	0.1	0.2	24	1.66
1345930	Rock	0.85	0.005	0.5	35.4	8.6	59	<0.1	29.9	12.9	277	3.34	8.4	3.4	18.9	21	<0.1	0.2	0.3	26	0.64
1345931	Rock	0.87	0.022	0.4	19.6	5.8	45	<0.1	22.9	14.0	602	3.07	28.7	3.5	17.6	16	<0.1	0.5	0.2	28	0.18
1345932	Rock	1.17	0.024	0.6	25.2	9.1	40	<0.1	18.7	13.5	740	2.76	41.6	27.1	11.7	41	<0.1	0.8	0.2	17	1.44
1345933	Rock	1.38	0.050	0.7	22.6	18.1	54	0.1	21.7	12.9	641	3.07	43.1	32.7	11.9	47	0.1	1.4	0.1	33	3.37
1345934	Rock	1.08	0.061	10.9	17.7	25.0	55	0.2	32.0	17.4	1815	4.36	73.7	27.6	5.5	125	0.1	1.0	0.3	30	8.59
1345935	Rock	1.36	0.035	1.1	8.0	12.0	28	<0.1	8.7	4.2	667	2.38	51.1	27.7	9.7	70	<0.1	0.7	0.1	22	1.07
1345936	Rock	0.87	0.023	1.1	13.1	6.5	33	<0.1	13.6	6.1	683	1.71	12.9	10.7	9.8	48	0.1	0.6	<0.1	22	1.34
1345937	Rock	0.96	0.007	1.5	43.7	19.2	73	0.2	31.8	11.1	590	2.46	29.0	4.6	5.8	65	0.4	1.0	0.4	48	1.52
1345938	Rock	0.91	0.010	2.7	54.3	22.9	88	0.2	36.9	13.3	647	2.86	33.3	5.6	7.6	83	0.5	1.3	0.5	57	2.33
1345939	Rock	1.00	0.108	1.3	31.7	14.7	57	0.1	27.8	11.2	522	2.42	23.0	6.5	4.9	66	0.3	1.0	0.2	43	1.40
1345940	Rock	0.71	<0.005	0.5	30.2	6.6	65	0.1	23.0	9.8	490	2.29	7.9	2.4	5.2	64	0.4	0.5	0.1	52	1.64
1345941	Rock	1.21	<0.005	1.0	23.5	8.9	44	0.1	19.3	7.4	453	1.89	11.9	2.3	5.3	49	0.2	0.7	0.2	37	1.16
1345942	Rock	0.97	<0.005	1.3	37.2	10.0	86	0.1	35.7	13.4	653	3.03	14.3	1.9	7.2	57	0.4	0.7	0.2	53	1.39
1345943	Rock	1.16	0.006	0.9	25.2	9.2	50	0.1	23.2	7.9	540	2.05	14.3	1.6	5.1	36	0.3	0.7	0.2	38	0.56
1345944	Rock	1.15	<0.005	0.7	22.4	7.8	37	<0.1	20.0	7.2	511	1.61	13.5	0.6	3.6	35	0.2	0.7	0.1	35	0.37



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1338735	Rock	0.038	11	160	0.77	2057	0.046	<20	1.14	0.050	0.25	0.5	2.16	12.8	0.9	<0.05	4	<0.5	<0.2	
1338736	Rock	0.055	3	72	1.81	439	0.188	<20	2.33	0.051	1.28	<0.1	0.29	12.8	0.4	<0.05	8	<0.5	<0.2	
1338737	Rock	0.043	6	68	0.54	1287	0.018	<20	1.16	0.018	0.33	0.7	2.24	20.3	1.5	<0.05	4	<0.5	<0.2	
1338738	Rock	0.020	2	16	0.10	2377	0.003	<20	0.60	0.003	0.11	0.5	1.23	23.0	0.5	0.06	2	<0.5	<0.2	
1338739	Rock	0.016	3	27	0.13	4129	0.005	<20	0.65	0.008	0.06	1.4	2.21	14.4	1.1	0.11	2	<0.5	<0.2	
1338740	Rock	0.089	13	32	2.00	681	0.205	<20	2.61	0.021	1.58	0.1	0.13	17.4	0.3	<0.05	9	<0.5	<0.2	
1338741	Rock	0.066	8	36	0.88	439	0.049	<20	1.54	0.036	0.61	0.1	0.14	16.0	0.2	<0.05	7	<0.5	<0.2	
1338742	Rock	0.060	4	7	1.21	287	0.134	<20	1.56	0.135	0.48	0.2	0.03	13.1	0.1	<0.05	7	<0.5	<0.2	
1338743	Rock	0.052	8	24	0.65	2525	0.044	<20	1.17	0.025	0.77	0.7	0.12	17.4	0.3	<0.05	5	<0.5	<0.2	
1338744	Rock	0.020	9	11	0.09	536	0.001	<20	0.45	0.005	0.25	0.3	0.20	4.9	0.1	<0.05	2	<0.5	<0.2	
1338745	Rock	0.006	2	9	0.09	2416	<0.001	<20	0.38	0.004	0.21	0.1	0.83	13.4	0.2	0.06	<1	<0.5	0.3	
1345926	Rock	0.035	53	17	0.59	170	0.098	<20	1.24	0.015	0.89	<0.1	0.04	3.8	0.4	<0.05	4	<0.5	<0.2	
1345927	Rock	0.024	7	10	0.20	233	0.003	<20	0.54	0.008	0.25	0.1	0.22	3.0	0.1	<0.05	2	<0.5	<0.2	
1345928	Rock	0.019	28	10	0.12	197	0.006	<20	0.59	0.007	0.30	0.2	0.08	3.5	<0.1	<0.05	2	<0.5	<0.2	
1345929	Rock	0.024	32	25	0.49	224	0.094	<20	0.95	0.030	0.46	<0.1	0.01	3.0	0.2	<0.05	5	<0.5	<0.2	
1345930	Rock	0.042	60	25	0.93	204	0.184	<20	1.79	0.016	1.31	<0.1	<0.01	4.2	0.6	<0.05	5	<0.5	<0.2	
1345931	Rock	0.039	43	25	0.98	295	0.165	<20	1.60	0.028	1.32	0.1	0.02	5.5	0.5	<0.05	6	<0.5	<0.2	
1345932	Rock	0.027	23	10	0.19	1136	0.008	<20	0.65	0.009	0.45	<0.1	0.05	4.8	0.1	<0.05	2	<0.5	<0.2	
1345933	Rock	0.044	28	17	0.18	612	0.006	<20	0.68	0.018	0.42	<0.1	0.21	7.5	0.2	<0.05	3	<0.5	<0.2	
1345934	Rock	0.062	13	14	0.25	3764	0.001	<20	0.56	0.005	0.28	0.3	0.38	17.8	0.2	0.09	1	<0.5	0.3	
1345935	Rock	0.041	19	8	0.13	3550	0.003	<20	0.56	0.017	0.25	0.2	0.48	5.4	0.1	0.08	1	<0.5	<0.2	
1345936	Rock	0.049	22	15	0.29	857	0.029	<20	0.67	0.029	0.20	<0.1	0.12	2.9	<0.1	<0.05	2	<0.5	<0.2	
1345937	Rock	0.096	17	35	0.72	388	0.075	<20	1.07	0.048	0.19	0.2	0.03	5.5	0.1	<0.05	3	<0.5	<0.2	
1345938	Rock	0.115	21	41	0.95	309	0.089	<20	1.33	0.049	0.22	0.2	0.03	6.2	0.2	<0.05	5	<0.5	<0.2	
1345939	Rock	0.087	16	33	0.66	312	0.069	<20	0.92	0.053	0.17	0.1	0.03	4.7	0.1	<0.05	3	<0.5	<0.2	
1345940	Rock	0.095	19	30	0.69	247	0.129	<20	1.32	0.066	0.20	0.2	0.04	4.8	0.1	<0.05	5	<0.5	<0.2	
1345941	Rock	0.053	16	22	0.47	242	0.061	<20	0.83	0.056	0.18	0.3	0.02	3.3	<0.1	<0.05	3	<0.5	<0.2	
1345942	Rock	0.085	22	38	0.91	409	0.078	<20	1.48	0.034	0.27	<0.1	0.06	5.9	0.2	<0.05	5	<0.5	<0.2	
1345943	Rock	0.066	14	23	0.50	262	0.061	<20	0.93	0.050	0.20	0.1	0.04	3.8	0.1	<0.05	3	<0.5	<0.2	
1345944	Rock	0.062	11	18	0.46	236	0.052	<20	0.74	0.048	0.15	<0.1	0.03	3.0	<0.1	<0.05	3	<0.5	<0.2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1345945	Rock	1.08	<0.005	1.6	32.7	12.3	73	0.1	29.7	11.6	890	2.90	44.7	2.1	7.4	53	0.3	1.2	0.3	45	1.34	
1345946	Rock	1.39	<0.005	1.2	13.7	10.6	42	<0.1	4.8	3.6	901	2.37	127.2	<0.5	8.3	51	0.1	1.3	<0.1	7	6.09	
1345947	Rock	1.12	0.007	1.0	15.0	19.9	52	<0.1	8.9	5.6	298	2.33	106.0	5.0	9.4	59	0.2	1.1	0.3	13	0.38	
1345948	Rock	1.15	0.030	0.7	19.1	13.4	43	<0.1	14.1	5.6	248	2.35	96.9	20.0	8.7	55	0.1	1.2	0.1	21	0.28	
1345999	Rock	1.03	0.089	6.3	23.5	15.2	33	0.2	32.3	9.3	342	2.26	23.0	216.4	19.6	82	0.1	1.0	<0.1	22	0.38	
1346000	Rock	0.85	0.119	5.7	41.5	26.4	67	0.3	40.4	10.7	818	2.77	21.7	141.1	40.4	81	0.3	3.4	0.2	38	0.23	
1347947	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	
1347948	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	
1347949	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	
1347950	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	
1347951	Rock	1.51	0.100	1.1	13.5	28.9	58	0.2	8.7	7.5	782	2.40	6.1	96.8	11.2	52	0.2	1.2	0.4	37	1.08	
1347952	Rock	1.17	0.067	1.2	11.0	11.2	36	0.1	4.2	4.7	499	1.95	3.9	50.3	8.6	55	0.1	0.9	0.2	23	0.66	
1347953	Rock	1.30	0.209	3.0	16.9	37.4	68	0.7	6.4	6.2	617	2.46	5.4	200.2	9.3	74	0.2	1.5	0.3	32	0.60	
1347954	Rock	1.38	0.382	2.6	21.4	47.7	130	1.0	10.2	9.1	717	3.24	8.3	304.7	8.7	75	0.4	2.1	0.2	49	0.65	
1347955	Rock	1.15	2.364	7.9	30.6	106.5	173	4.8	9.0	8.6	607	4.07	19.2	2386.3	8.0	107	0.7	2.5	0.4	31	0.24	
1347956	Rock	0.85	0.307	3.6	18.4	49.4	97	0.8	11.5	9.2	628	3.82	30.6	268.8	7.0	60	0.3	1.3	0.2	44	0.56	
1347957	Rock	1.55	0.275	2.6	12.8	53.0	22	0.4	3.6	7.6	82	3.21	4.4	326.7	8.0	84	0.3	1.3	0.2	17	0.11	
1347958	Rock	1.55	0.006	1.9	22.2	41.0	52	<0.1	2.9	3.6	361	2.21	8.2	8.4	9.7	52	0.1	4.0	0.3	11	0.17	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000140.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1345945	Rock	0.068	19	30	0.56	1967	0.045	<20	1.29	0.023	0.27	<0.1	0.29	5.7	0.2	<0.05	4	<0.5	<0.2
1345946	Rock	0.027	10	3	0.13	1541	<0.001	<20	0.45	0.002	0.21	<0.1	0.10	5.5	<0.1	<0.05	1	<0.5	<0.2
1345947	Rock	0.032	11	9	0.17	3959	0.004	<20	0.64	0.012	0.27	<0.1	0.45	4.2	0.1	0.09	2	<0.5	<0.2
1345948	Rock	0.023	15	12	0.20	3159	0.006	<20	0.80	0.010	0.22	0.1	0.39	4.4	0.2	0.07	2	<0.5	<0.2
1345999	Rock	0.052	16	16	0.10	1030	0.004	<20	0.58	0.012	0.27	0.1	0.10	5.8	0.1	<0.05	2	<0.5	<0.2
1346000	Rock	0.050	19	20	0.14	1082	0.008	<20	0.85	0.008	0.27	<0.1	0.20	7.6	0.1	<0.05	2	<0.5	<0.2
1347947	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
1347948	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
1347949	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
1347950	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
1347951	Rock	0.050	22	16	0.31	889	0.029	<20	0.71	0.053	0.32	0.2	0.09	8.3	0.1	<0.05	3	<0.5	<0.2
1347952	Rock	0.038	22	8	0.16	1340	0.022	<20	0.47	0.046	0.25	0.2	0.06	6.8	<0.1	<0.05	2	<0.5	<0.2
1347953	Rock	0.055	24	11	0.13	2227	0.007	<20	0.47	0.054	0.18	0.2	0.35	9.8	<0.1	<0.05	2	<0.5	0.7
1347954	Rock	0.046	20	18	0.12	1953	0.004	<20	0.53	0.057	0.19	<0.1	0.22	14.2	<0.1	<0.05	2	<0.5	0.9
1347955	Rock	0.041	18	11	0.10	4058	0.003	<20	0.49	0.048	0.13	0.1	0.66	14.4	<0.1	0.10	2	0.8	7.4
1347956	Rock	0.050	15	16	0.20	1875	0.004	<20	0.78	0.024	0.18	1.1	0.37	13.2	<0.1	<0.05	3	<0.5	0.9
1347957	Rock	0.040	28	5	0.04	3912	0.002	<20	0.31	0.081	0.07	0.1	0.33	6.6	<0.1	0.10	<1	0.7	0.7
1347958	Rock	0.013	12	4	0.08	1872	0.003	<20	0.51	0.024	0.22	0.3	0.26	5.2	0.1	<0.05	2	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 12, 2016

Page: 1 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000140.1

Method	Analyte	Unit	MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200				
				Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca		
				kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm			
				0.01	0.005	0.1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1			
Pulp Duplicates																									
REP 1338678	QC					0.9	4.3	7.7	22	<0.1	4.6	4.4	683	1.40	7.1	<0.5	7.3	18	<0.1	0.2	0.4	16	0.20		
REP 1338712	QC					0.2	56.9	5.6	89	<0.1	41.1	12.8	554	3.57	4.0	<0.5	7.6	54	<0.1	0.2	<0.1	91	0.30		
1338713	Rock					1.02	<0.005	0.3	22.5	5.5	53	<0.1	11.9	6.5	300	2.13	3.0	<0.5	4.1	29	<0.1	0.1	<0.1	30	0.31
REP 1338713	QC					<0.005																			
1338714	Rock					0.91	0.008	<0.1	162.2	1.3	76	<0.1	18.9	23.0	741	4.35	3.0	1.9	0.6	58	<0.1	0.1	<0.1	191	1.48
REP 1338714	QC					0.005																			
1345927	Rock					0.97	<0.005	0.3	16.5	6.6	17	<0.1	8.9	6.2	346	1.36	6.2	3.7	10.4	63	<0.1	0.4	<0.1	11	3.19
REP 1345927	QC					0.4 15.5 6.6 17 <0.1 8.9 6.0 354 1.40 6.1 2.9 9.9 63 <0.1 0.5 <0.1 11 3.29																			
1347958	Rock					1.55	0.006	1.9	22.2	41.0	52	<0.1	2.9	3.6	361	2.21	8.2	8.4	9.7	52	0.1	4.0	0.3	11	0.17
REP 1347958	QC					2.0 21.4 40.3 52 <0.1 3.0 3.4 358 2.22 7.7 7.8 8.7 48 0.3 3.9 0.3 12 0.17																			
Core Reject Duplicates																									
1338678	Rock					0.85	<0.005	1.2	4.5	8.4	23	<0.1	5.2	4.7	699	1.43	7.4	<0.5	8.0	21	<0.1	0.2	0.4	16	0.20
DUP 1338678	QC					<0.005 1.3 4.9 9.0 24 <0.1 5.6 4.9 710 1.50 7.3 2.5 8.8 23 <0.1 0.2 0.5 17 0.20																			
1338712	Rock					0.96	<0.005	0.2	55.2	5.4	89	<0.1	40.1	13.7	533	3.44	3.6	<0.5	7.3	50	<0.1	0.2	<0.1	90	0.29
DUP 1338712	QC					<0.005 0.2 51.2 5.4 86 <0.1 39.0 13.3 533 3.44 3.8 <0.5 7.2 49 <0.1 0.1 <0.1 89 0.29																			
1345926	Rock					1.29	<0.005	0.7	20.3	6.9	69	<0.1	24.1	14.9	393	2.67	1.8	4.9	22.8	13	<0.1	0.2	<0.1	19	0.28
DUP 1345926	QC					<0.005 0.7 18.4 6.5 62 <0.1 20.9 12.4 376 2.52 1.7 4.4 20.8 11 <0.1 0.2 <0.1 18 0.27																			
1347956	Rock					0.85	0.307	3.6	18.4	49.4	97	0.8	11.5	9.2	628	3.82	30.6	268.8	7.0	60	0.3	1.3	0.2	44	0.56
DUP 1347956	QC					0.301 3.6 20.2 50.4 103 0.7 11.9 9.7 626 3.85 33.1 260.6 7.5 65 0.3 1.5 0.2 43 0.55																			
Reference Materials																									
STD DS10	Standard																								
						15.3	151.5	137.8	373	1.8	79.3	13.2	880	2.79	45.6	53.1	6.8	64	2.7	7.7	12.0	46	1.09		
STD DS10	Standard					14.7	154.6	157.4	376	2.0	82.6	14.3	920	2.84	45.7	52.9	7.2	66	2.6	7.3	12.3	46	1.13		
STD DS10	Standard					15.5	168.9	157.4	390	1.9	85.3	14.3	910	2.82	46.1	61.5	7.3	68	2.3	7.4	11.7	46	1.12		
STD DS10	Standard					15.4	155.1	143.0	368	1.8	78.4	13.2	887	2.84	44.2	56.2	7.2	64	2.6	7.2	10.7	45	1.08		
STD OREAS45EA	Standard					1.7	689.1	13.5	32	0.3	398.7	54.9	395	21.08	11.2	57.9	9.6	4	<0.1	0.2	0.2	312	0.03		
STD OREAS45EA	Standard					1.8	698.5	14.0	31	0.3	406.1	52.9	401	22.18	10.1	53.7	9.8	4	<0.1	0.2	0.2	316	0.03		
STD OREAS45EA	Standard					1.5	681.1	14.2	32	0.3	389.2	52.1	387	21.09	10.5	48.1	9.3	3	<0.1	0.3	0.2	306	0.03		
STD OREAS45EA	Standard					1.6	719.1	14.6	33	0.3	389.5	53.1	419	21.56	11.5	57.2	9.7	4	<0.1	0.3	0.3	311	0.03		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Project: QV
Report Date: August 12, 2016

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000140.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
REP 1338678	QC	0.038	6	6	0.15	366	0.002	<20	0.71	0.021	0.30	<0.1	0.02	6.0	<0.1	<0.05	2	<0.5	<0.2
REP 1338712	QC	0.050	22	66	1.25	950	0.198	<20	1.82	0.035	1.10	0.1	0.02	6.7	0.5	<0.05	8	<0.5	<0.2
1338713	Rock	0.028	18	18	0.72	469	0.117	<20	1.35	0.042	0.62	0.1	0.01	3.8	0.3	<0.05	5	<0.5	<0.2
REP 1338713	QC																		
1338714	Rock	0.087	6	14	1.59	544	0.221	<20	2.23	0.233	0.84	<0.1	0.03	12.9	0.2	<0.05	8	<0.5	<0.2
REP 1338714	QC																		
1345927	Rock	0.024	7	10	0.20	233	0.003	<20	0.54	0.008	0.25	0.1	0.22	3.0	0.1	<0.05	2	<0.5	<0.2
REP 1345927	QC	0.025	7	11	0.21	232	0.003	<20	0.54	0.009	0.26	<0.1	0.21	3.0	<0.1	<0.05	2	<0.5	<0.2
1347958	Rock	0.013	12	4	0.08	1872	0.003	<20	0.51	0.024	0.22	0.3	0.26	5.2	0.1	<0.05	2	<0.5	<0.2
REP 1347958	QC	0.012	11	3	0.08	1726	0.003	<20	0.50	0.023	0.22	0.2	0.26	5.2	0.1	<0.05	2	<0.5	<0.2
Core Reject Duplicates																			
1338678	Rock	0.045	7	7	0.17	429	0.002	<20	0.73	0.021	0.31	<0.1	0.02	7.1	<0.1	<0.05	3	<0.5	<0.2
DUP 1338678	QC	0.050	8	8	0.18	466	0.002	<20	0.86	0.025	0.37	<0.1	0.02	6.8	<0.1	<0.05	3	<0.5	<0.2
1338712	Rock	0.048	22	61	1.22	917	0.196	<20	1.75	0.029	1.05	0.2	0.02	7.4	0.4	<0.05	8	<0.5	<0.2
DUP 1338712	QC	0.047	20	63	1.20	930	0.191	<20	1.75	0.035	1.06	0.1	0.02	7.1	0.4	<0.05	8	<0.5	<0.2
1345926	Rock	0.035	53	17	0.59	170	0.098	<20	1.24	0.015	0.89	<0.1	0.04	3.8	0.4	<0.05	4	<0.5	<0.2
DUP 1345926	QC	0.032	47	15	0.56	158	0.095	<20	1.18	0.014	0.83	<0.1	0.03	3.5	0.3	<0.05	4	<0.5	<0.2
1347956	Rock	0.050	15	16	0.20	1875	0.004	<20	0.78	0.024	0.18	1.1	0.37	13.2	<0.1	<0.05	3	<0.5	0.9
DUP 1347956	QC	0.052	16	18	0.20	1809	0.004	<20	0.79	0.025	0.18	1.2	0.41	14.3	<0.1	<0.05	3	<0.5	0.9
Reference Materials																			
STD DS10	Standard	0.075	18	54	0.80	403	0.086	<20	1.06	0.071	0.34	3.2	0.30	3.0	5.1	0.30	5	2.2	4.8
STD DS10	Standard	0.081	19	59	0.82	428	0.084	<20	1.12	0.075	0.35	2.8	0.28	3.3	5.3	0.30	5	3.1	5.1
STD DS10	Standard	0.073	18	61	0.82	439	0.090	<20	1.07	0.072	0.35	3.3	0.32	3.0	5.7	0.31	5	2.4	4.8
STD DS10	Standard	0.069	17	55	0.78	403	0.085	<20	1.05	0.072	0.34	3.1	0.28	3.2	5.0	0.28	4	2.0	4.4
STD OREAS45EA	Standard	0.027	7	856	0.10	130	0.101	<20	3.39	0.020	0.06	<0.1	0.01	77.3	<0.1	<0.05	13	1.9	<0.2
STD OREAS45EA	Standard	0.029	7	849	0.10	136	0.099	<20	3.41	0.021	0.06	<0.1	<0.01	76.0	<0.1	<0.05	13	1.1	<0.2
STD OREAS45EA	Standard	0.026	7	807	0.10	136	0.098	<20	3.28	0.019	0.06	<0.1	0.02	79.4	<0.1	<0.05	13	1.0	<0.2
STD OREAS45EA	Standard	0.026	7	846	0.10	140	0.102	<20	3.45	0.026	0.06	<0.1	0.02	77.0	<0.1	<0.05	13	1.0	<0.2



QUALITY CONTROL REPORT

WHI16000140.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OXD108	Standard		0.421																		
STD OXD108	Standard		0.407																		
STD OXI121	Standard		1.827																		
STD OXI121	Standard		1.809																		
STD OXN117	Standard		7.735																		
STD OXN117	Standard		7.658																		
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.6	6.6	1.5	36	<0.1	7.6	4.1	432	1.81	0.7	<0.5	2.2	29	<0.1	<0.1	<0.1	25	0.69
ROCK-WHI	Prep Blank		<0.005	0.7	8.7	2.5	62	<0.1	7.3	4.4	448	1.85	1.2	0.8	2.2	26	0.1	<0.1	<0.1	25	0.70



QUALITY CONTROL REPORT

WHI16000140.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXD108	Standard																			
STD OXD108	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.02	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
Prep Wash																				
ROCK-WHI	Prep Blank	0.036	6	11	0.48	70	0.102	<20	1.00	0.091	0.10	0.1	<0.01	3.3	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.036	6	10	0.47	69	0.098	<20	1.02	0.108	0.12	0.2	<0.01	3.1	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 02, 2016
Report Date: August 11, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000142.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV-2016-07-26-Rock-GTP
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1
CANADA

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	138	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method Analyte	Unit	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
MDL		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1347959	Rock	1.28	0.012	2.3	7.1	12.7	58	<0.1	2.9	4.2	749	2.53	17.3	12.9	15.4	47	0.3	1.6	<0.1	27	0.19	
1347960	Rock	0.95	0.006	2.7	9.1	6.5	41	<0.1	2.5	4.0	1042	2.30	11.2	9.1	9.6	45	0.2	2.0	0.1	14	0.23	
1347961	Rock	1.24	0.071	1.7	21.1	18.7	39	0.2	7.0	3.1	221	3.12	156.3	74.1	8.8	91	<0.1	2.4	<0.1	22	0.59	
1347962	Rock	1.04	0.320	2.0	12.8	18.0	27	0.7	4.3	2.5	146	2.60	269.0	485.5	8.6	134	0.1	10.4	<0.1	21	0.14	
1347963	Rock	0.82	0.047	1.7	8.0	6.1	45	<0.1	4.8	5.2	815	2.02	44.9	46.6	7.1	42	0.2	1.6	0.2	9	0.20	
1347964	Rock	1.28	0.098	1.5	15.1	8.8	31	0.2	4.0	2.9	203	1.88	19.3	91.0	12.4	49	<0.1	2.7	0.2	16	0.32	
1347965	Rock	0.51	0.029	1.0	12.4	8.9	26	<0.1	5.2	2.9	131	1.23	16.7	24.5	10.3	65	<0.1	2.0	0.1	18	0.30	
1347966	Rock	1.13	0.038	2.0	20.0	6.2	28	<0.1	9.2	3.9	552	1.77	55.9	48.1	10.9	133	0.1	2.2	<0.1	21	2.86	
1347967	Rock	1.66	0.079	1.6	13.4	9.7	35	<0.1	3.6	4.2	588	2.77	19.5	62.0	9.8	36	0.2	2.2	0.1	12	0.16	
1347968	Rock	0.96	0.106	3.6	9.2	13.9	51	<0.1	2.4	5.3	1210	3.68	65.7	29.1	7.7	38	0.1	1.1	0.1	8	0.23	
1347969	Rock	0.95	0.011	1.2	7.3	10.4	22	<0.1	2.5	2.1	404	1.63	16.8	10.9	10.4	43	<0.1	1.0	0.1	6	0.45	
1347970	Rock	0.83	0.011	3.8	12.4	12.8	53	<0.1	7.4	6.4	2217	3.66	12.6	7.8	9.8	55	0.2	1.8	<0.1	20	0.26	
1347971	Rock	0.98	0.015	2.0	23.2	14.9	45	<0.1	6.3	6.3	1376	2.82	15.9	9.2	8.0	67	0.2	3.4	0.2	22	0.16	
1390451	Rock	1.66	0.010	1.8	49.3	14.6	115	0.2	42.3	14.5	560	3.25	24.6	4.1	7.3	57	0.5	1.1	0.3	62	1.29	
1390452	Rock	0.99	0.005	0.9	31.9	10.6	72	0.1	27.7	10.8	507	2.55	18.3	5.2	5.5	53	0.4	0.8	0.1	42	1.00	
1390453	Rock	1.07	0.006	1.0	31.2	10.4	65	0.1	25.7	11.2	388	2.58	25.7	3.1	5.2	51	0.4	0.9	0.1	45	0.58	
1390454	Rock	1.49	0.029	1.0	27.1	10.7	45	<0.1	24.2	13.7	1007	3.87	120.3	26.1	10.2	74	0.1	2.3	0.3	59	0.41	
1390455	Rock	1.04	0.010	1.4	30.6	9.6	52	<0.1	23.1	10.8	597	2.81	63.3	7.2	6.9	63	0.2	1.5	0.2	48	1.58	
1390456	Rock	0.93	0.043	1.9	41.6	13.1	49	0.2	33.0	13.5	778	3.08	311.7	43.8	6.3	39	0.2	8.7	0.1	45	0.42	
1390457	Rock	1.14	0.006	0.8	26.0	7.9	51	<0.1	24.7	10.2	475	2.40	26.5	4.5	4.6	83	0.3	0.8	0.1	47	2.58	
1390458	Rock	1.07	0.025	1.5	32.8	10.2	59	0.1	26.6	12.6	629	2.97	82.6	16.6	5.3	68	0.2	2.0	0.1	53	1.65	
1390459	Rock	1.09	0.051	2.0	39.3	11.9	55	0.2	39.0	18.7	1348	4.38	361.5	52.2	6.7	65	0.3	2.5	0.5	71	0.98	
1390460	Rock	1.20	0.012	1.8	46.9	14.3	55	<0.1	31.7	10.8	694	3.12	125.4	9.3	5.6	42	0.1	2.2	0.2	33	0.31	
1390461	Rock	0.90	0.005	2.5	80.9	18.5	73	<0.1	36.9	13.6	1136	4.07	79.1	3.4	6.6	43	0.1	2.4	0.2	35	0.23	
1390462	Rock	0.98	0.007	1.6	52.9	10.6	63	<0.1	29.7	12.7	1052	3.27	56.6	3.6	5.5	52	0.1	2.5	0.1	40	0.66	
1390463	Rock	1.31	0.007	1.0	33.4	39.8	74	<0.1	26.0	8.2	126	2.75	29.7	4.4	13.1	27	<0.1	1.7	0.4	22	0.17	
1390464	Rock	1.13	<0.005	0.9	32.2	36.2	78	<0.1	20.0	6.3	88	2.54	39.1	2.7	9.8	27	<0.1	3.2	0.2	19	0.13	
1390465	Rock	1.05	<0.005	1.7	31.7	17.6	56	<0.1	24.9	10.0	254	3.41	73.0	1.2	7.2	73	0.1	4.8	0.1	19	0.17	
1390466	Rock	0.99	<0.005	1.6	42.7	27.5	78	<0.1	25.7	10.3	287	3.36	98.3	<0.5	10.8	55	0.1	57.1	0.2	23	0.19	
1390467	Rock	1.32	<0.005	1.7	16.9	19.5	43	<0.1	14.4	6.7	206	2.10	83.6	1.2	4.7	49	<0.1	8.3	0.2	10	0.09	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**

310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV

Report Date: August 11, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1347959	Rock	0.039	28	3	0.04	1458	0.002	<20	0.45	0.075	0.18	0.5	0.42	5.2	0.1	<0.05	2	<0.5	<0.2
1347960	Rock	0.022	15	2	0.10	1002	0.006	<20	0.52	0.043	0.24	0.2	0.32	4.5	0.2	<0.05	2	<0.5	<0.2
1347961	Rock	0.012	13	6	0.11	3380	0.003	<20	0.62	0.056	0.17	0.7	0.50	3.7	<0.1	0.13	2	0.8	0.4
1347962	Rock	0.022	19	4	0.04	2768	<0.001	<20	0.41	0.085	0.14	1.0	0.67	4.8	0.1	0.15	2	<0.5	0.7
1347963	Rock	0.014	18	3	0.09	1265	0.002	<20	0.69	0.027	0.31	0.1	0.37	4.6	0.2	<0.05	2	<0.5	<0.2
1347964	Rock	0.020	27	5	0.07	1639	0.002	<20	0.42	0.060	0.11	0.2	0.29	4.2	<0.1	<0.05	2	<0.5	0.3
1347965	Rock	0.015	21	8	0.08	4477	0.005	<20	0.50	0.055	0.13	0.2	0.47	3.0	0.1	0.09	2	<0.5	<0.2
1347966	Rock	0.014	22	6	0.16	3383	0.002	<20	0.64	0.051	0.09	1.0	0.42	3.7	<0.1	0.08	2	<0.5	<0.2
1347967	Rock	0.034	18	4	0.07	1335	0.003	<20	0.71	0.039	0.28	0.2	0.41	4.0	0.2	<0.05	3	<0.5	<0.2
1347968	Rock	0.055	17	3	0.06	2304	<0.001	<20	0.65	0.015	0.24	0.1	0.29	3.5	0.1	<0.05	2	<0.5	<0.2
1347969	Rock	0.020	16	3	0.06	831	<0.001	<20	0.47	0.060	0.15	<0.1	0.14	2.1	<0.1	<0.05	2	<0.5	<0.2
1347970	Rock	0.022	18	9	0.12	4848	0.003	<20	0.67	0.039	0.18	<0.1	0.23	4.6	0.1	0.09	3	<0.5	<0.2
1347971	Rock	0.029	14	8	0.13	4263	0.002	<20	0.59	0.033	0.23	0.1	0.28	5.4	0.1	0.09	2	<0.5	<0.2
1390451	Rock	0.082	20	39	0.84	547	0.052	<20	1.96	0.035	0.34	0.1	0.09	6.5	0.2	<0.05	6	<0.5	<0.2
1390452	Rock	0.074	19	27	0.65	756	0.067	<20	1.43	0.045	0.20	0.2	0.08	4.1	0.1	<0.05	4	<0.5	<0.2
1390453	Rock	0.058	18	25	0.51	783	0.060	<20	1.58	0.050	0.18	0.1	0.06	3.9	0.1	<0.05	5	<0.5	<0.2
1390454	Rock	0.075	23	29	0.32	4112	0.014	<20	1.50	0.016	0.43	<0.1	0.43	12.4	0.3	0.08	5	<0.5	<0.2
1390455	Rock	0.062	18	24	0.46	1041	0.040	<20	1.37	0.042	0.24	<0.1	0.15	6.6	0.2	<0.05	4	<0.5	<0.2
1390456	Rock	0.077	18	38	0.22	942	0.013	<20	1.04	0.014	0.27	<0.1	0.49	7.7	0.2	<0.05	3	<0.5	<0.2
1390457	Rock	0.065	16	30	0.67	523	0.070	<20	1.27	0.056	0.16	0.1	0.04	4.5	0.1	<0.05	4	<0.5	<0.2
1390458	Rock	0.073	17	29	0.57	930	0.055	<20	1.48	0.047	0.20	<0.1	0.13	6.2	0.2	<0.05	4	<0.5	<0.2
1390459	Rock	0.104	19	29	0.40	2242	0.012	<20	1.55	0.019	0.33	<0.1	0.36	16.8	0.2	<0.05	4	<0.5	<0.2
1390460	Rock	0.034	15	23	0.20	1241	0.010	<20	1.02	0.012	0.29	<0.1	0.16	6.9	0.1	<0.05	3	<0.5	<0.2
1390461	Rock	0.037	17	20	0.16	1298	0.006	<20	0.96	0.013	0.27	<0.1	0.31	8.8	0.2	<0.05	3	<0.5	<0.2
1390462	Rock	0.058	16	25	0.37	1162	0.028	<20	1.12	0.025	0.33	<0.1	0.12	6.2	0.2	<0.05	4	<0.5	<0.2
1390463	Rock	0.048	28	23	0.20	379	0.021	<20	1.34	0.027	0.44	<0.1	0.12	5.9	0.2	<0.05	4	<0.5	<0.2
1390464	Rock	0.029	14	16	0.12	537	0.008	<20	0.99	0.021	0.36	<0.1	0.13	4.7	0.1	<0.05	3	<0.5	<0.2
1390465	Rock	0.036	14	15	0.13	4638	0.005	<20	0.93	0.014	0.37	<0.1	0.14	6.0	0.1	0.09	3	<0.5	<0.2
1390466	Rock	0.055	21	14	0.14	124	0.006	<20	1.02	0.020	0.51	<0.1	0.10	6.6	0.2	<0.05	4	0.9	<0.2
1390467	Rock	0.007	6	8	0.08	1327	0.001	<20	0.60	0.007	0.35	<0.1	0.18	3.8	0.1	<0.05	2	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1390468	Rock	1.46	<0.005	2.6	22.6	13.1	67	<0.1	20.5	10.2	632	3.19	55.8	<0.5	9.5	31	<0.1	3.1	0.1	13	0.10
1390469	Rock	1.28	0.009	2.7	35.8	21.1	77	<0.1	27.9	14.6	643	3.27	111.4	16.4	6.5	43	<0.1	3.0	0.2	14	0.13
1392926	Rock	1.28	0.018	0.5	25.8	6.8	60	<0.1	22.4	11.6	591	3.03	7.6	4.2	15.7	17	<0.1	0.4	0.1	29	0.19
1392927	Rock	1.49	0.009	0.9	15.6	6.1	29	<0.1	16.4	6.8	289	2.07	6.8	1.4	17.6	24	<0.1	0.5	<0.1	22	0.15
1392928	Rock	0.58	<0.005	1.6	40.3	17.4	74	<0.1	31.6	10.2	693	2.35	26.1	3.1	6.1	36	0.4	1.2	0.3	43	0.51
1392929	Rock	1.92	<0.005	0.9	43.9	5.2	90	<0.1	41.7	17.3	417	4.85	15.5	1.9	15.5	19	<0.1	1.2	0.2	32	0.17
1392930	Rock	0.93	0.010	1.1	20.6	5.0	82	<0.1	35.4	17.9	654	3.93	5.8	10.4	15.8	30	<0.1	0.3	0.1	31	0.35
1392931	Rock	1.07	0.046	1.1	35.9	5.0	77	<0.1	35.4	16.3	815	3.54	9.5	2.8	16.0	19	<0.1	0.4	0.1	23	0.22
1392932	Rock	1.84	0.007	0.8	42.1	5.9	94	<0.1	48.1	19.6	604	4.27	11.3	3.1	16.0	19	<0.1	0.5	0.1	37	0.19
1392933	Rock	1.32	0.013	0.7	38.6	9.3	58	<0.1	36.5	17.2	683	3.95	21.1	7.2	13.5	27	<0.1	1.1	<0.1	54	0.18
1392934	Rock	1.58	0.013	0.7	35.4	10.9	54	<0.1	28.1	11.1	541	3.02	67.3	9.6	13.6	31	<0.1	1.9	0.2	30	0.17
1392935	Rock	1.26	0.007	0.6	29.3	10.3	52	<0.1	27.2	10.1	592	2.90	116.8	3.9	10.5	34	<0.1	2.8	0.1	34	0.20
1392936	Rock	1.26	0.009	0.7	37.2	15.1	51	0.1	29.5	10.0	658	3.22	41.1	8.9	12.5	31	<0.1	1.3	0.2	37	0.24
1392937	Rock	1.13	0.007	1.3	29.8	7.3	42	<0.1	25.1	10.6	476	2.91	17.0	3.0	18.4	19	<0.1	0.8	<0.1	36	0.17
1392938	Rock	1.60	0.073	1.1	28.7	10.0	52	0.3	29.7	13.4	658	3.56	54.2	60.1	8.3	44	<0.1	2.3	0.1	36	0.18
1392939	Rock	1.48	0.108	2.7	30.7	8.9	30	0.2	28.9	11.1	943	2.96	216.4	94.6	5.2	69	<0.1	3.4	0.2	28	0.15
1418251	Rock	1.60	<0.005	1.6	47.5	32.4	96	0.2	30.7	19.3	1166	4.33	2.8	0.5	2.2	19	<0.1	0.1	0.2	63	0.18
1418252	Rock	1.18	<0.005	0.3	81.8	11.4	108	0.2	19.5	23.8	961	5.42	2.1	<0.5	2.8	27	0.3	<0.1	0.2	111	0.46
1418253	Rock	0.95	<0.005	0.4	25.7	5.7	59	<0.1	5.4	6.4	462	2.66	3.5	<0.5	3.1	24	<0.1	0.2	<0.1	22	0.16
1418254	Rock	0.95	<0.005	0.3	17.8	3.5	39	<0.1	14.8	9.1	290	2.50	3.8	<0.5	6.2	37	<0.1	0.2	<0.1	22	0.69
1418255	Rock	1.38	<0.005	0.3	29.8	8.9	68	<0.1	17.3	12.4	286	1.82	3.2	1.2	5.6	25	0.5	0.1	0.2	13	0.17
1418256	Rock	1.14	0.016	0.7	13.0	17.5	20	0.4	3.2	1.9	239	0.97	7.6	16.5	2.8	33	0.1	0.5	<0.1	3	0.06
1418257	Rock	1.66	0.047	0.4	10.5	13.5	20	0.3	3.0	1.9	192	1.00	5.6	43.9	1.7	35	0.1	0.4	<0.1	5	0.08
1418258	Rock	1.05	0.047	0.8	17.7	10.9	21	0.5	5.7	3.4	453	1.39	8.1	48.1	2.2	51	0.1	0.3	<0.1	7	0.06
1418259	Rock	1.04	0.104	0.9	12.4	6.8	30	0.5	4.3	3.8	363	1.64	10.5	98.5	6.7	46	<0.1	0.3	<0.1	11	0.10
1418260	Rock	1.47	0.074	0.6	15.6	4.5	34	0.2	6.1	6.3	533	1.93	3.8	75.8	6.5	28	<0.1	0.4	<0.1	9	0.11
1418261	Rock	1.42	0.122	0.6	12.2	7.5	39	0.3	5.1	5.0	654	2.21	3.6	110.1	7.3	36	0.1	0.2	<0.1	9	0.11
1418262	Rock	1.75	0.063	0.5	16.3	8.1	31	0.6	4.6	4.3	482	1.71	7.1	62.8	6.6	58	<0.1	1.4	<0.1	10	0.10
1418263	Rock	1.64	0.041	0.9	14.7	6.6	27	0.4	6.8	6.3	425	1.67	6.4	40.1	5.1	35	<0.1	1.0	<0.1	13	0.09
1418264	Rock	1.77	0.031	0.4	11.3	3.7	16	0.1	3.5	3.1	478	1.15	3.8	28.1	2.8	35	<0.1	0.9	<0.1	5	0.04



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1390468	Rock	0.024	15	9	0.08	239	0.002	<20	0.64	0.015	0.40	<0.1	0.08	4.4	0.2	<0.05	2	<0.5	<0.2
1390469	Rock	0.022	10	11	0.08	612	0.001	<20	0.62	0.012	0.33	<0.1	0.13	5.4	0.2	<0.05	2	<0.5	<0.2
1392926	Rock	0.027	30	25	0.72	407	0.120	<20	1.68	0.030	0.99	<0.1	0.03	4.6	0.4	<0.05	5	<0.5	<0.2
1392927	Rock	0.029	29	21	0.33	523	0.068	<20	0.94	0.038	0.45	<0.1	0.03	3.9	0.2	<0.05	3	<0.5	<0.2
1392928	Rock	0.081	16	32	0.57	255	0.057	<20	1.07	0.051	0.20	0.2	0.02	4.7	0.1	<0.05	4	<0.5	<0.2
1392929	Rock	0.055	59	29	0.63	344	0.105	<20	1.91	0.015	1.07	<0.1	0.08	7.9	0.4	<0.05	5	<0.5	<0.2
1392930	Rock	0.035	48	27	0.71	579	0.112	<20	1.64	0.022	1.06	0.2	0.04	6.3	0.4	<0.05	5	<0.5	<0.2
1392931	Rock	0.045	47	24	0.48	318	0.028	<20	1.41	0.024	0.42	0.2	0.03	6.4	0.1	<0.05	4	<0.5	<0.2
1392932	Rock	0.046	56	37	0.67	321	0.089	<20	1.84	0.024	0.92	0.1	0.05	7.4	0.4	<0.05	6	<0.5	<0.2
1392933	Rock	0.042	44	37	0.33	415	0.050	<20	1.25	0.052	0.43	<0.1	0.14	9.9	0.2	<0.05	4	<0.5	<0.2
1392934	Rock	0.036	54	26	0.24	502	0.019	<20	1.26	0.008	0.45	<0.1	0.16	7.6	0.2	<0.05	3	<0.5	<0.2
1392935	Rock	0.029	45	27	0.24	607	0.015	<20	1.14	0.007	0.35	<0.1	0.17	7.2	0.2	<0.05	3	<0.5	<0.2
1392936	Rock	0.049	42	33	0.35	415	0.031	<20	1.75	0.010	0.48	<0.1	0.22	8.7	0.2	<0.05	5	<0.5	<0.2
1392937	Rock	0.039	44	29	0.33	241	0.057	<20	1.19	0.031	0.51	<0.1	0.08	6.5	0.2	<0.05	4	<0.5	<0.2
1392938	Rock	0.025	28	26	0.21	938	0.012	<20	1.31	0.013	0.36	<0.1	0.79	9.8	0.2	<0.05	3	<0.5	<0.2
1392939	Rock	0.017	17	19	0.17	2072	0.006	<20	1.07	0.006	0.30	<0.1	0.49	9.0	0.2	<0.05	3	<0.5	0.3
1418251	Rock	0.029	6	65	0.11	663	0.002	<20	0.71	0.042	0.29	<0.1	0.10	21.3	<0.1	<0.05	3	<0.5	<0.2
1418252	Rock	0.115	7	34	0.14	411	0.003	<20	0.95	0.032	0.44	<0.1	0.04	25.5	0.1	<0.05	5	<0.5	<0.2
1418253	Rock	0.038	7	5	0.05	583	0.001	<20	0.50	0.049	0.21	<0.1	0.11	4.5	<0.1	<0.05	2	<0.5	<0.2
1418254	Rock	0.021	8	16	0.11	680	0.008	<20	0.63	0.047	0.37	<0.1	0.10	4.6	0.1	<0.05	3	<0.5	<0.2
1418255	Rock	0.013	10	7	0.06	2673	0.001	<20	0.49	0.011	0.34	<0.1	0.05	3.9	<0.1	0.06	1	<0.5	<0.2
1418256	Rock	0.015	3	4	0.02	320	<0.001	<20	0.40	0.016	0.27	<0.1	0.05	1.2	<0.1	<0.05	1	<0.5	0.3
1418257	Rock	0.018	6	3	0.04	408	0.001	<20	0.40	0.055	0.17	<0.1	0.04	1.7	<0.1	<0.05	1	<0.5	0.5
1418258	Rock	0.021	9	4	0.02	686	0.001	<20	0.35	0.069	0.19	<0.1	0.02	2.8	<0.1	<0.05	1	<0.5	0.4
1418259	Rock	0.032	21	4	0.04	363	0.002	<20	0.39	0.055	0.20	<0.1	0.05	4.5	<0.1	<0.05	1	<0.5	1.3
1418260	Rock	0.035	21	4	0.05	929	0.002	<20	0.46	0.052	0.23	<0.1	0.04	4.4	<0.1	<0.05	1	<0.5	<0.2
1418261	Rock	0.035	22	3	0.04	679	0.001	<20	0.45	0.048	0.23	<0.1	0.02	4.0	<0.1	<0.05	1	<0.5	0.4
1418262	Rock	0.025	19	6	0.06	824	0.005	<20	0.40	0.039	0.18	<0.1	0.02	4.0	<0.1	<0.05	1	<0.5	0.5
1418263	Rock	0.022	15	9	0.10	348	0.010	<20	0.51	0.033	0.22	<0.1	0.03	4.3	<0.1	<0.05	1	<0.5	0.5
1418264	Rock	0.008	7	3	0.03	340	0.001	<20	0.33	0.039	0.18	<0.1	0.01	2.3	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1418265	Rock	1.40	0.069	0.6	11.7	8.9	22	0.4	4.3	3.1	277	1.38	9.2	66.8	5.7	39	<0.1	0.5	<0.1	9	0.05
1418266	Rock	1.19	0.110	1.0	11.2	22.2	19	1.1	3.6	2.1	111	2.74	22.5	105.2	5.1	47	<0.1	0.9	<0.1	13	0.06
1418267	Rock	1.38	0.086	0.9	9.9	22.9	8	0.7	2.6	1.1	72	1.42	18.7	94.6	2.9	41	<0.1	0.6	<0.1	8	0.04
1418268	Rock	1.57	0.093	0.8	28.7	9.5	49	0.8	10.6	16.1	808	3.00	23.4	82.4	2.1	40	<0.1	0.7	<0.1	44	0.10
1418269	Rock	1.64	0.040	0.7	27.1	5.4	46	0.4	13.1	12.0	708	2.37	16.4	34.3	1.2	39	<0.1	0.3	<0.1	44	0.09
1418270	Rock	1.70	0.029	2.9	17.0	15.4	26	0.4	6.2	5.5	284	1.47	16.2	26.4	3.2	32	<0.1	0.5	0.3	20	0.06
1418271	Rock	1.03	0.050	1.5	12.2	16.1	17	0.6	2.8	1.0	76	1.17	18.3	46.9	4.1	54	<0.1	0.4	<0.1	11	0.06
1418272	Rock	1.12	0.025	1.7	10.8	14.5	17	0.3	4.3	2.9	188	1.02	18.8	23.8	2.9	31	<0.1	0.5	<0.1	14	0.08
1418273	Rock	1.04	0.050	1.6	5.8	8.3	6	0.4	2.5	0.8	56	0.81	27.4	46.9	2.3	40	<0.1	0.4	<0.1	10	0.03
1418274	Rock	1.71	0.031	5.3	11.1	19.5	16	0.3	4.5	1.6	77	1.49	24.1	34.4	3.1	36	<0.1	0.6	0.1	14	0.07
1418275	Rock	1.38	0.045	3.1	14.0	14.6	21	0.5	6.3	3.0	125	1.55	33.4	41.9	3.9	34	<0.1	0.7	0.1	26	0.12
1418276	Rock	1.29	0.031	2.7	10.0	14.3	14	0.3	5.3	2.3	101	1.18	26.5	56.1	2.5	30	<0.1	0.4	<0.1	18	0.09
1418277	Rock	1.25	0.032	19.2	13.4	20.8	17	0.4	6.8	2.4	99	1.32	24.5	33.8	2.3	34	<0.1	0.4	0.4	21	0.10
1418278	Rock	1.52	0.040	27.2	20.0	18.3	39	0.3	6.7	2.8	98	1.77	23.9	37.4	2.5	29	<0.1	0.3	<0.1	21	0.13
1418279	Rock	1.30	0.015	6.0	12.1	16.8	18	0.2	8.2	4.4	134	1.48	20.9	12.8	2.0	35	<0.1	0.4	0.1	27	0.17
1418280	Rock	1.77	0.048	7.1	9.5	18.8	22	0.4	5.0	2.6	89	1.10	24.2	50.5	2.0	43	<0.1	0.3	0.1	15	0.07
1418281	Rock	1.79	0.036	5.1	13.1	17.3	30	0.3	5.3	2.7	146	1.36	15.0	32.8	2.2	37	<0.1	0.4	<0.1	19	0.11
1418282	Rock	1.47	0.022	5.6	10.3	16.7	16	0.3	4.6	2.2	97	1.01	15.5	19.1	1.8	33	<0.1	0.8	0.1	15	0.08
1418283	Rock	1.22	0.012	5.4	10.9	16.4	17	0.2	5.8	3.3	161	1.17	16.2	7.9	1.7	28	<0.1	0.7	<0.1	18	0.10
1418284	Rock	1.40	0.007	16.4	7.8	7.7	10	0.1	4.3	2.2	85	0.89	9.3	5.4	1.4	27	<0.1	0.5	<0.1	13	0.06
1418302	Rock	1.22	<0.005	0.6	18.6	5.7	60	<0.1	7.0	8.8	421	3.15	4.0	<0.5	4.2	23	<0.1	0.3	<0.1	35	0.13
1418303	Rock	1.16	<0.005	0.5	24.8	67.1	26	0.4	4.1	3.5	210	1.14	11.8	<0.5	4.1	44	0.1	1.0	1.4	10	0.81
1418304	Rock	1.21	<0.005	0.3	9.5	12.7	34	0.1	11.0	5.5	333	1.73	2.2	0.8	2.7	28	<0.1	0.2	0.2	22	0.18
1418305	Rock	1.07	<0.005	0.9	60.5	4.4	67	<0.1	4.7	9.5	440	2.88	0.9	0.9	6.0	62	0.1	<0.1	0.1	34	1.88
1418306	Rock	1.75	<0.005	0.4	17.4	5.1	56	<0.1	16.9	7.1	426	2.24	5.2	<0.5	5.7	58	<0.1	<0.1	<0.1	33	1.08
1418307	Rock	1.55	<0.005	0.4	18.5	2.4	50	<0.1	5.3	4.6	326	2.03	3.7	<0.5	5.9	24	<0.1	0.1	<0.1	25	0.18
1418308	Rock	0.89	<0.005	0.3	12.1	3.4	57	<0.1	8.0	4.8	330	1.76	6.6	<0.5	2.7	88	<0.1	<0.1	<0.1	25	0.94
1418309	Rock	1.14	<0.005	0.3	4.6	12.5	55	<0.1	5.8	6.1	1143	2.53	1.3	<0.5	2.5	79	0.2	<0.1	0.2	33	3.78
1418310	Rock	1.72	<0.005	0.2	57.4	6.5	107	<0.1	26.2	22.4	985	5.60	2.7	0.6	4.0	126	<0.1	<0.1	0.2	92	5.01
1418311	Rock	1.20	0.011	2.6	32.8	19.7	86	0.2	18.6	14.5	1231	5.03	28.0	8.6	1.6	157	0.3	0.2	0.2	69	7.15



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1418265	Rock	0.025	17	5	0.03	470	0.002	<20	0.39	0.032	0.30	<0.1	0.01	3.6	<0.1	0.07	1	<0.5	0.5	
1418266	Rock	0.039	19	5	0.04	443	0.006	<20	0.36	0.009	0.44	<0.1	0.04	4.6	<0.1	0.41	1	1.6	1.4	
1418267	Rock	0.017	10	5	0.02	632	0.003	<20	0.36	0.009	0.38	0.1	0.02	2.3	<0.1	0.15	1	1.0	1.0	
1418268	Rock	0.017	5	8	0.09	1105	0.004	<20	0.54	0.017	0.28	<0.1	0.05	10.9	<0.1	<0.05	2	<0.5	0.4	
1418269	Rock	0.009	3	13	0.11	1322	0.004	<20	0.63	0.044	0.26	0.1	0.03	10.5	<0.1	<0.05	2	<0.5	0.2	
1418270	Rock	0.009	9	6	0.06	1025	0.004	<20	0.42	0.030	0.17	<0.1	0.02	4.3	<0.1	<0.05	1	0.5	0.4	
1418271	Rock	0.008	4	4	0.03	359	0.002	<20	0.42	0.009	0.24	0.1	0.02	2.3	<0.1	<0.05	2	1.4	0.4	
1418272	Rock	0.010	6	7	0.07	479	0.013	<20	0.35	0.017	0.13	0.2	0.02	2.5	<0.1	<0.05	1	0.7	0.5	
1418273	Rock	0.004	4	9	0.02	519	0.005	<20	0.23	0.011	0.25	0.2	0.01	0.7	<0.1	0.13	<1	0.7	0.6	
1418274	Rock	0.009	5	12	0.06	802	0.021	<20	0.37	0.017	0.24	<0.1	0.02	1.5	<0.1	0.19	2	0.9	0.6	
1418275	Rock	0.012	10	11	0.11	384	0.040	<20	0.51	0.022	0.19	<0.1	0.02	2.1	0.1	0.14	2	1.0	0.6	
1418276	Rock	0.008	7	10	0.08	541	0.027	<20	0.43	0.019	0.18	<0.1	0.02	1.8	<0.1	0.11	2	0.9	0.6	
1418277	Rock	0.010	6	12	0.09	727	0.027	<20	0.50	0.021	0.15	<0.1	<0.01	2.2	<0.1	0.07	2	<0.5	0.5	
1418278	Rock	0.022	7	9	0.09	303	0.021	<20	0.71	0.026	0.17	<0.1	0.02	3.0	<0.1	0.10	2	<0.5	0.3	
1418279	Rock	0.020	6	15	0.18	704	0.033	<20	0.68	0.022	0.16	0.1	<0.01	2.3	<0.1	0.09	2	<0.5	<0.2	
1418280	Rock	0.014	6	9	0.07	389	0.020	<20	0.39	0.025	0.17	0.1	<0.01	1.8	<0.1	0.12	1	0.8	0.5	
1418281	Rock	0.018	7	10	0.09	352	0.029	<20	0.48	0.033	0.16	<0.1	<0.01	2.7	<0.1	0.11	1	<0.5	0.3	
1418282	Rock	0.012	5	9	0.07	677	0.017	<20	0.38	0.027	0.16	<0.1	<0.01	1.8	<0.1	0.08	1	<0.5	0.3	
1418283	Rock	0.011	6	11	0.08	443	0.027	<20	0.40	0.025	0.14	<0.1	<0.01	1.5	<0.1	<0.05	1	0.6	0.3	
1418284	Rock	0.009	4	9	0.05	369	0.011	<20	0.35	0.030	0.14	<0.1	<0.01	1.3	<0.1	<0.05	1	<0.5	<0.2	
1418302	Rock	0.017	7	8	0.15	1166	0.005	<20	0.81	0.029	0.32	<0.1	0.81	9.6	0.1	<0.05	5	<0.5	<0.2	
1418303	Rock	0.032	2	7	0.20	1450	<0.001	<20	0.41	0.027	0.16	<0.1	0.64	2.4	<0.1	<0.05	2	<0.5	<0.2	
1418304	Rock	0.032	5	17	0.07	909	0.002	<20	0.52	0.042	0.18	<0.1	0.21	6.0	<0.1	<0.05	2	<0.5	<0.2	
1418305	Rock	0.056	10	8	0.56	558	0.002	<20	0.49	0.041	0.21	<0.1	0.15	8.3	<0.1	0.05	3	<0.5	<0.2	
1418306	Rock	0.035	13	39	0.37	375	0.007	<20	0.53	0.051	0.24	<0.1	0.23	8.1	0.1	<0.05	3	<0.5	<0.2	
1418307	Rock	0.034	13	11	0.20	371	0.020	<20	0.62	0.061	0.29	<0.1	0.07	5.8	0.1	<0.05	4	<0.5	<0.2	
1418308	Rock	0.025	5	15	0.38	818	0.007	<20	0.42	0.065	0.14	<0.1	0.15	5.1	<0.1	<0.05	2	<0.5	<0.2	
1418309	Rock	0.021	3	7	1.27	1989	<0.001	<20	0.25	0.033	0.11	<0.1	0.79	4.2	<0.1	0.07	<1	<0.5	<0.2	
1418310	Rock	0.091	5	26	2.02	1184	0.001	<20	0.63	0.037	0.25	<0.1	0.13	12.4	<0.1	0.06	2	<0.5	<0.2	
1418311	Rock	0.004	3	15	3.33	1084	<0.001	<20	0.66	0.043	0.29	<0.1	0.13	11.1	0.1	<0.05	2	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1418312	Rock	1.23	0.019	4.8	21.4	28.2	29	0.3	3.8	3.3	384	1.45	7.5	37.8	9.1	22	<0.1	<0.1	0.4	6	0.20
1418313	Rock	1.52	0.060	1.1	12.0	12.0	27	0.2	2.6	2.9	509	1.60	17.3	69.0	12.3	20	<0.1	0.1	<0.1	7	0.66
1418314	Rock	1.57	0.030	2.1	11.3	6.7	37	0.2	3.1	2.9	345	1.63	11.8	27.8	7.6	18	<0.1	<0.1	0.1	7	0.10
1418315	Rock	1.70	0.007	1.7	27.3	6.9	76	<0.1	6.3	13.4	868	4.13	2.1	7.2	12.2	58	<0.1	<0.1	<0.1	28	1.24
1418316	Rock	1.49	<0.005	1.2	14.6	10.0	48	<0.1	4.5	7.6	730	3.24	1.3	3.9	10.0	87	<0.1	<0.1	0.2	24	2.60
1418317	Rock	2.06	<0.005	0.8	15.4	12.4	44	<0.1	3.5	7.1	862	2.78	1.7	5.3	11.3	100	<0.1	<0.1	0.1	22	2.96
1418318	Rock	1.37	<0.005	0.6	12.3	8.9	35	<0.1	3.6	10.5	646	2.70	2.3	4.2	8.7	77	0.1	<0.1	0.1	15	2.22
1418319	Rock	0.81	<0.005	1.3	29.6	4.5	65	<0.1	18.6	13.3	608	3.22	1.1	3.0	3.8	71	<0.1	<0.1	0.1	14	2.65
1418320	Rock	1.31	0.071	4.1	16.1	34.0	40	0.6	8.0	7.0	587	2.08	32.6	63.5	4.9	85	0.2	0.2	0.4	7	2.05
1418321	Rock	1.21	0.025	9.4	45.5	28.3	55	0.5	25.8	15.4	697	2.88	33.2	21.1	1.6	104	0.2	0.3	0.5	15	2.64
1418322	Rock	0.76	0.019	4.4	34.0	16.7	50	0.3	22.6	12.5	753	2.95	19.7	16.4	2.3	122	0.2	0.2	0.3	15	3.47
1418323	Rock	1.18	<0.005	0.8	19.4	4.4	39	<0.1	10.0	9.3	546	2.29	7.0	2.9	2.6	87	<0.1	0.1	<0.1	10	2.42
1418324	Rock	1.26	0.038	5.9	45.2	12.5	37	0.9	20.1	11.1	508	2.27	37.6	36.7	2.9	34	0.2	0.7	0.3	10	0.60
1418325	Rock	1.48	0.059	11.9	52.0	23.6	40	1.2	47.6	18.2	850	2.61	58.9	52.0	2.4	40	0.3	0.5	0.4	15	0.93
1418326	Rock	1.50	0.020	1.0	21.9	8.8	14	0.3	4.7	2.6	244	0.96	8.0	18.6	2.3	49	<0.1	0.2	0.1	6	0.06
1418327	Rock	1.64	0.041	1.8	109.2	23.5	20	1.2	4.2	2.6	352	1.45	12.0	31.1	3.6	46	<0.1	0.4	0.6	6	0.05
1418328	Rock	1.38	0.023	0.4	24.3	7.4	19	0.4	5.5	4.1	263	1.55	12.9	20.9	7.8	31	<0.1	0.3	0.1	8	0.08
1418329	Rock	1.17	0.027	44.9	39.9	13.9	15	1.1	2.4	3.6	365	1.73	8.9	25.5	5.1	80	0.2	0.7	0.4	5	0.07
1418330	Rock	0.98	0.023	8.4	20.7	18.4	15	0.8	2.5	5.1	661	2.22	6.9	20.3	6.4	56	0.1	0.2	0.3	7	0.10
1418331	Rock	0.93	0.037	3.4	43.1	17.5	19	1.1	3.2	4.8	588	2.14	7.6	30.9	6.0	36	<0.1	0.4	0.3	8	0.11
1418332	Rock	1.06	0.054	2.1	29.6	30.7	25	1.6	3.8	9.8	1018	2.80	17.4	53.3	6.4	43	0.1	0.4	0.2	13	0.15
1418333	Rock	0.90	0.051	0.8	23.6	17.7	38	1.3	5.5	9.4	767	2.99	22.4	46.3	9.1	40	<0.1	0.3	0.2	13	0.34
1418334	Rock	1.21	0.035	2.0	56.2	15.1	22	1.1	7.0	6.0	407	2.43	15.5	34.8	7.1	29	0.1	0.4	0.3	13	0.12
1418335	Rock	1.67	0.032	4.9	51.4	23.8	24	1.2	5.9	6.7	671	2.12	11.7	35.1	4.5	42	0.2	0.4	0.3	13	0.72
1418336	Rock	1.29	0.016	3.2	158.8	24.2	18	1.1	6.0	3.8	503	1.24	32.4	11.0	2.3	31	0.2	2.5	0.5	9	0.09
1418337	Rock	1.84	0.022	2.7	71.5	15.7	24	1.4	4.5	4.4	535	1.85	17.0	21.3	4.7	35	0.1	0.6	0.3	12	0.10
1418338	Rock	0.98	0.033	1.9	57.6	18.6	21	0.4	15.3	6.0	564	1.58	10.9	27.4	3.2	32	<0.1	0.5	0.2	17	0.13
1418339	Rock	1.32	0.013	0.6	33.9	8.6	14	0.3	4.2	2.8	428	1.27	7.1	10.0	2.6	41	<0.1	0.3	0.2	8	0.06
1418340	Rock	1.45	0.018	3.3	47.1	6.3	37	0.5	5.3	6.2	674	2.37	13.5	15.9	4.9	31	<0.1	0.5	0.3	18	0.09
1418341	Rock	1.15	0.015	0.8	36.2	6.1	33	0.6	4.7	4.8	519	1.83	28.2	21.4	4.7	30	0.1	0.5	0.2	17	0.11



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method Analyte Unit MDL		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1418312	Rock	0.025	25	6	0.09	1291	0.001	<20	0.29	0.045	0.13	<0.1	0.09	3.2	<0.1	0.08	<1	<0.5	<0.2	
1418313	Rock	0.028	26	4	0.23	84	<0.001	<20	0.35	0.038	0.19	<0.1	0.07	2.3	<0.1	<0.05	<1	<0.5	<0.2	
1418314	Rock	0.019	16	6	0.05	379	<0.001	<20	0.29	0.054	0.11	<0.1	0.06	2.7	<0.1	<0.05	<1	<0.5	<0.2	
1418315	Rock	0.074	18	10	0.10	391	0.002	<20	0.51	0.025	0.32	<0.1	0.04	9.2	<0.1	<0.05	2	<0.5	<0.2	
1418316	Rock	0.046	27	6	0.15	475	0.002	<20	0.41	0.034	0.23	<0.1	0.02	4.1	<0.1	<0.05	1	<0.5	<0.2	
1418317	Rock	0.050	33	5	0.94	154	<0.001	<20	0.43	0.036	0.26	<0.1	0.03	4.9	<0.1	<0.05	2	<0.5	<0.2	
1418318	Rock	0.037	16	6	0.62	588	<0.001	<20	0.39	0.037	0.25	<0.1	0.06	3.3	<0.1	0.08	1	<0.5	<0.2	
1418319	Rock	0.004	10	9	0.94	934	<0.001	<20	0.36	0.010	0.25	<0.1	0.09	3.7	<0.1	<0.05	<1	<0.5	<0.2	
1418320	Rock	0.013	10	4	0.61	1858	<0.001	<20	0.37	0.007	0.22	<0.1	0.27	2.8	<0.1	0.07	<1	<0.5	0.4	
1418321	Rock	0.010	1	5	0.59	581	<0.001	<20	0.46	0.007	0.25	<0.1	0.27	7.5	0.1	<0.05	<1	<0.5	0.2	
1418322	Rock	0.007	2	7	0.68	472	<0.001	<20	0.49	0.008	0.24	<0.1	0.23	5.6	0.1	<0.05	1	<0.5	<0.2	
1418323	Rock	0.010	3	7	0.51	711	<0.001	<20	0.43	0.015	0.25	<0.1	0.12	3.7	<0.1	<0.05	<1	<0.5	<0.2	
1418324	Rock	0.023	8	6	0.20	584	<0.001	<20	0.38	0.007	0.22	<0.1	0.25	4.5	<0.1	<0.05	<1	<0.5	0.3	
1418325	Rock	0.018	4	8	0.49	1285	<0.001	<20	0.44	0.005	0.24	<0.1	0.37	6.5	0.1	<0.05	<1	0.6	0.4	
1418326	Rock	0.009	6	6	0.03	1616	0.001	<20	0.25	0.036	0.16	<0.1	0.03	1.7	<0.1	<0.05	<1	<0.5	0.3	
1418327	Rock	0.014	11	5	0.03	797	0.001	<20	0.27	0.015	0.17	<0.1	0.03	2.7	<0.1	<0.05	<1	0.8	0.7	
1418328	Rock	0.025	19	5	0.03	489	0.001	<20	0.33	0.024	0.20	<0.1	0.03	3.3	<0.1	<0.05	<1	<0.5	0.5	
1418329	Rock	0.026	21	5	0.02	551	0.001	<20	0.22	0.006	0.21	<0.1	0.04	3.5	<0.1	0.14	<1	0.7	0.3	
1418330	Rock	0.038	45	4	0.03	510	0.001	<20	0.28	0.005	0.24	<0.1	0.04	4.4	<0.1	0.19	<1	<0.5	0.4	
1418331	Rock	0.037	19	4	0.03	328	0.001	<20	0.34	0.016	0.24	<0.1	0.04	4.0	<0.1	0.11	<1	1.3	0.3	
1418332	Rock	0.050	18	4	0.05	572	0.001	<20	0.31	0.008	0.25	0.1	0.06	7.4	<0.1	0.12	<1	1.6	0.9	
1418333	Rock	0.044	24	5	0.10	319	0.001	<20	0.36	0.018	0.25	0.1	0.07	6.6	<0.1	0.07	1	1.9	0.4	
1418334	Rock	0.035	24	6	0.07	313	0.005	<20	0.48	0.015	0.25	<0.1	0.04	3.9	<0.1	<0.05	1	<0.5	0.6	
1418335	Rock	0.035	12	12	0.05	397	0.002	<20	0.36	0.024	0.22	0.1	0.04	4.9	<0.1	<0.05	1	1.1	0.5	
1418336	Rock	0.015	8	6	0.05	500	0.005	<20	0.33	0.022	0.19	<0.1	0.02	2.3	<0.1	<0.05	1	<0.5	0.5	
1418337	Rock	0.025	14	8	0.05	336	0.005	<20	0.32	0.019	0.20	<0.1	0.03	2.9	<0.1	<0.05	1	<0.5	0.6	
1418338	Rock	0.008	12	12	0.12	389	0.013	<20	0.59	0.017	0.14	<0.1	0.06	4.1	<0.1	<0.05	2	<0.5	0.4	
1418339	Rock	0.011	4	6	0.05	216	0.001	<20	0.30	0.022	0.17	<0.1	0.05	2.3	<0.1	<0.05	<1	<0.5	0.3	
1418340	Rock	0.029	14	6	0.05	299	0.002	<20	0.36	0.023	0.18	<0.1	0.05	6.0	<0.1	<0.05	1	1.0	0.3	
1418341	Rock	0.026	9	5	0.04	225	0.002	<20	0.32	0.031	0.18	<0.1	0.03	4.9	<0.1	<0.05	1	0.8	0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1418342	Rock	1.49	0.016	1.6	55.4	24.4	25	0.5	3.7	3.3	412	1.21	19.3	15.2	2.5	31	<0.1	0.7	0.3	10	0.08
1418343	Rock	1.91	0.029	2.1	34.9	14.3	24	0.5	6.7	4.0	510	1.31	12.7	18.5	2.0	34	0.2	0.8	0.2	15	0.12
1418344	Rock	1.25	0.019	1.2	36.1	11.4	32	0.5	5.4	6.2	666	1.66	14.4	14.3	3.6	26	0.1	0.5	0.2	17	0.15
1418345	Rock	1.46	0.011	1.9	45.1	24.5	35	0.8	6.6	6.1	677	2.41	13.6	11.4	6.1	26	0.2	0.6	0.3	15	0.11
1418346	Rock	1.54	0.036	2.1	25.9	26.5	21	0.8	5.4	5.0	579	1.36	9.5	27.2	4.9	39	<0.1	0.8	0.2	11	0.10
1418347	Rock	1.48	0.020	2.2	56.8	13.7	35	0.6	9.1	6.6	568	2.12	14.6	13.5	4.4	34	0.1	0.8	0.2	23	0.16
1418366	Rock	1.70	<0.005	0.4	11.2	2.3	43	<0.1	15.6	13.0	519	3.09	0.8	<0.5	5.4	53	<0.1	<0.1	<0.1	33	2.01
1418367	Rock	1.33	<0.005	1.0	21.7	3.3	31	<0.1	19.9	12.5	613	2.80	3.8	<0.5	5.2	103	<0.1	0.1	0.2	17	6.46
1418368	Rock	1.05	0.101	0.8	53.8	12.5	114	3.2	9.8	18.4	334	4.30	44.6	93.1	0.8	57	<0.1	0.5	0.2	44	0.17
1418369	Rock	1.90	0.038	2.7	49.3	27.4	78	1.3	8.6	8.8	287	3.05	31.7	37.2	6.4	40	0.1	1.5	0.2	19	0.06
1418370	Rock	1.25	0.007	0.5	30.6	4.2	85	0.1	11.7	32.6	1622	7.54	2.0	4.0	0.5	138	0.3	0.2	<0.1	153	6.06
1418371	Rock	1.29	<0.005	0.3	53.1	2.5	67	<0.1	7.4	31.4	1240	6.96	1.7	0.8	0.5	225	0.1	0.1	<0.1	144	4.84
1418372	Rock	1.06	0.019	0.6	53.5	2.7	72	0.6	8.7	33.1	1399	7.11	5.7	14.2	0.5	93	0.2	0.3	<0.1	223	5.06
1418373	Rock	1.17	<0.005	0.4	33.3	4.1	60	<0.1	13.5	32.9	1676	7.13	1.1	1.2	0.4	97	0.1	<0.1	<0.1	128	5.81
1418374	Rock	1.09	0.050	4.1	43.7	31.5	63	1.1	5.0	5.3	1123	2.58	10.1	50.2	1.0	29	0.2	1.8	0.3	19	0.18
1418375	Rock	1.42	0.033	17.9	141.6	109.8	84	1.6	4.8	7.1	692	2.31	9.2	27.7	1.6	22	0.3	1.0	0.9	10	0.04
1418376	Rock	0.99	0.027	4.9	93.6	55.2	40	1.9	4.6	3.8	165	2.70	29.2	23.7	2.0	44	0.3	5.4	0.7	11	0.06
1418377	Rock	1.20	0.025	0.8	33.8	18.5	41	0.8	3.0	5.0	512	2.34	5.0	21.2	1.9	29	0.3	0.8	0.1	11	0.08



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000142.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1418342	Rock	0.020	6	8	0.04	260	0.006	<20	0.34	0.030	0.18	<0.1	0.03	2.8	<0.1	<0.05	1	<0.5	0.4	
1418343	Rock	0.016	7	11	0.08	360	0.019	<20	0.45	0.029	0.16	<0.1	0.05	2.9	<0.1	<0.05	1	<0.5	0.3	
1418344	Rock	0.031	12	9	0.08	353	0.017	<20	0.48	0.046	0.18	<0.1	0.04	3.9	<0.1	<0.05	1	0.7	<0.2	
1418345	Rock	0.037	18	6	0.05	353	0.004	<20	0.36	0.026	0.21	<0.1	0.06	5.7	<0.1	<0.05	1	0.6	0.4	
1418346	Rock	0.015	6	8	0.06	1063	0.011	<20	0.42	0.020	0.18	<0.1	0.09	2.8	<0.1	<0.05	1	<0.5	0.3	
1418347	Rock	0.028	13	12	0.13	497	0.021	<20	0.59	0.033	0.16	0.1	0.06	5.1	<0.1	<0.05	2	0.7	0.4	
1418366	Rock	0.035	9	11	0.44	568	0.002	<20	0.47	0.033	0.27	<0.1	0.47	3.7	<0.1	<0.05	2	<0.5	<0.2	
1418367	Rock	0.035	9	12	0.65	274	0.001	<20	0.43	0.023	0.28	<0.1	0.63	3.0	<0.1	0.15	1	<0.5	<0.2	
1418368	Rock	0.050	2	5	0.09	399	0.001	<20	0.80	0.019	0.45	<0.1	0.65	12.6	0.1	0.47	2	1.7	1.5	
1418369	Rock	0.037	19	4	0.04	252	<0.001	<20	0.55	0.013	0.41	<0.1	0.05	6.8	<0.1	0.47	<1	1.6	1.2	
1418370	Rock	0.069	6	8	1.38	537	0.005	<20	0.82	0.029	0.42	<0.1	0.03	25.3	<0.1	<0.05	3	<0.5	<0.2	
1418371	Rock	0.077	8	2	1.42	2223	0.005	<20	0.69	0.022	0.39	<0.1	0.01	20.9	<0.1	0.07	2	<0.5	<0.2	
1418372	Rock	0.086	7	6	1.42	89	0.056	<20	1.71	0.031	0.19	0.8	0.02	19.3	<0.1	<0.05	8	<0.5	0.5	
1418373	Rock	0.075	6	8	2.26	54	0.002	<20	0.78	0.028	0.39	<0.1	<0.01	23.7	<0.1	<0.05	2	<0.5	<0.2	
1418374	Rock	0.052	4	4	0.07	585	0.001	<20	0.40	0.028	0.20	<0.1	0.05	5.1	<0.1	0.05	1	0.7	0.6	
1418375	Rock	0.022	7	5	0.03	142	<0.001	<20	0.34	0.014	0.25	<0.1	0.13	7.4	<0.1	0.18	<1	1.7	1.1	
1418376	Rock	0.027	11	5	0.02	258	<0.001	<20	0.30	0.011	0.40	<0.1	0.35	8.7	<0.1	0.51	1	1.4	1.7	
1418377	Rock	0.029	7	4	0.04	552	<0.001	<20	0.26	0.024	0.18	<0.1	0.05	6.6	<0.1	<0.05	<1	1.0	0.5	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 1 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000142.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1347966	Rock	1.13	0.038	2.0	20.0	6.2	28	<0.1	9.2	3.9	552	1.77	55.9	48.1	10.9	133	0.1	2.2	<0.1	21	2.86
REP 1347966	QC	0.039																			
1347967	Rock	1.66	0.079	1.6	13.4	9.7	35	<0.1	3.6	4.2	588	2.77	19.5	62.0	9.8	36	0.2	2.2	0.1	12	0.16
REP 1347967	QC	0.061																			
1390467	Rock	1.32	<0.005	1.7	16.9	19.5	43	<0.1	14.4	6.7	206	2.10	83.6	1.2	4.7	49	<0.1	8.3	0.2	10	0.09
REP 1390467	QC	1.6 17.0 18.7 42 <0.1 14.4 6.5 203 2.02 81.7 <0.5 4.6 47 <0.1 7.7 0.2 10 0.09																			
1418267	Rock	1.38	0.086	0.9	9.9	22.9	8	0.7	2.6	1.1	72	1.42	18.7	94.6	2.9	41	<0.1	0.6	<0.1	8	0.04
REP 1418267	QC	0.6 9.7 22.8 8 0.6 2.4 0.9 69 1.32 16.9 82.7 2.6 38 <0.1 0.6 <0.1 8 0.03																			
1418304	Rock	1.21	<0.005	0.3	9.5	12.7	34	0.1	11.0	5.5	333	1.73	2.2	0.8	2.7	28	<0.1	0.2	0.2	22	0.18
REP 1418304	QC	<0.005																			
1418305	Rock	1.07	<0.005	0.9	60.5	4.4	67	<0.1	4.7	9.5	440	2.88	0.9	0.9	6.0	62	0.1	<0.1	0.1	34	1.88
REP 1418305	QC	<0.005																			
1418319	Rock	0.81	<0.005	1.3	29.6	4.5	65	<0.1	18.6	13.3	608	3.22	1.1	3.0	3.8	71	<0.1	<0.1	0.1	14	2.65
REP 1418319	QC	1.0 28.3 4.4 60 <0.1 17.3 12.5 615 3.29 1.7 3.2 3.6 72 <0.1 <0.1 <0.1 13 2.70																			
1418372	Rock	1.06	0.019	0.6	53.5	2.7	72	0.6	8.7	33.1	1399	7.11	5.7	14.2	0.5	93	0.2	0.3	<0.1	223	5.06
REP 1418372	QC	0.4 51.0 2.6 72 0.6 8.3 32.3 1392 7.06 6.1 15.1 0.4 85 0.1 0.3 <0.1 220 4.95																			
Core Reject Duplicates																					
1390460	Rock	1.20	0.012	1.8	46.9	14.3	55	<0.1	31.7	10.8	694	3.12	125.4	9.3	5.6	42	0.1	2.2	0.2	33	0.31
DUP 1390460	QC	0.012 1.9 48.2 14.8 56 <0.1 31.8 11.0 695 3.08 128.2 9.5 5.8 44 0.1 2.3 0.2 32 0.29																			
1418261	Rock	1.42	0.122	0.6	12.2	7.5	39	0.3	5.1	5.0	654	2.21	3.6	110.1	7.3	36	0.1	0.2	<0.1	9	0.11
DUP 1418261	QC	0.118 0.6 13.1 8.0 36 0.4 5.8 5.5 643 2.19 3.6 253.2 8.3 39 <0.1 0.2 <0.1 9 0.11																			
1418312	Rock	1.23	0.019	4.8	21.4	28.2	29	0.3	3.8	3.3	384	1.45	7.5	37.8	9.1	22	<0.1	<0.1	0.4	6	0.20
DUP 1418312	QC	0.017 4.2 19.5 29.5 28 0.3 3.9 3.3 387 1.51 7.0 17.2 8.4 19 <0.1 0.1 0.4 6 0.19																			
1418346	Rock	1.54	0.036	2.1	25.9	26.5	21	0.8	5.4	5.0	579	1.36	9.5	27.2	4.9	39	<0.1	0.8	0.2	11	0.10
DUP 1418346	QC	0.037 1.8 24.7 24.3 18 0.7 5.5 4.6 561 1.35 9.1 23.8 4.4 39 0.1 0.8 0.2 11 0.10																			
Reference Materials																					
STD DS10	Standard	13.5 155.2 142.2 367 1.8 74.6 12.8 865 2.69 49.1 95.1 6.6 61 2.8 7.9 10.7 39 1.06																			
STD DS10	Standard	13.6 153.2 139.8 361 1.9 73.5 13.0 920 2.78 48.6 56.2 6.8 61 2.5 7.4 11.1 42 1.08																			



QUALITY CONTROL REPORT

WHI16000142.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1347966	Rock	0.014	22	6	0.16	3383	0.002	<20	0.64	0.051	0.09	1.0	0.42	3.7	<0.1	0.08	2	<0.5	<0.2
REP 1347966	QC																		
1347967	Rock	0.034	18	4	0.07	1335	0.003	<20	0.71	0.039	0.28	0.2	0.41	4.0	0.2	<0.05	3	<0.5	<0.2
REP 1347967	QC																		
1390467	Rock	0.007	6	8	0.08	1327	0.001	<20	0.60	0.007	0.35	<0.1	0.18	3.8	0.1	<0.05	2	<0.5	<0.2
REP 1390467	QC	0.007	6	8	0.08	1304	<0.001	<20	0.57	0.007	0.35	<0.1	0.16	4.0	0.1	<0.05	1	<0.5	<0.2
1418267	Rock	0.017	10	5	0.02	632	0.003	<20	0.36	0.009	0.38	0.1	0.02	2.3	<0.1	0.15	1	1.0	1.0
REP 1418267	QC	0.016	8	4	0.02	628	0.003	<20	0.34	0.009	0.36	<0.1	0.02	2.1	<0.1	0.15	1	0.8	1.0
1418304	Rock	0.032	5	17	0.07	909	0.002	<20	0.52	0.042	0.18	<0.1	0.21	6.0	<0.1	<0.05	2	<0.5	<0.2
REP 1418304	QC																		
1418305	Rock	0.056	10	8	0.56	558	0.002	<20	0.49	0.041	0.21	<0.1	0.15	8.3	<0.1	0.05	3	<0.5	<0.2
REP 1418305	QC																		
1418319	Rock	0.004	10	9	0.94	934	<0.001	<20	0.36	0.010	0.25	<0.1	0.09	3.7	<0.1	<0.05	<1	<0.5	<0.2
REP 1418319	QC	0.004	10	9	0.95	884	<0.001	<20	0.36	0.012	0.26	<0.1	0.08	3.6	<0.1	<0.05	<1	<0.5	<0.2
1418372	Rock	0.086	7	6	1.42	89	0.056	<20	1.71	0.031	0.19	0.8	0.02	19.3	<0.1	<0.05	8	<0.5	0.5
REP 1418372	QC	0.083	6	6	1.43	85	0.052	<20	1.74	0.031	0.19	0.8	0.02	18.4	<0.1	<0.05	8	<0.5	0.3
Core Reject Duplicates																			
1390460	Rock	0.034	15	23	0.20	1241	0.010	<20	1.02	0.012	0.29	<0.1	0.16	6.9	0.1	<0.05	3	<0.5	<0.2
DUP 1390460	QC	0.035	15	23	0.19	1284	0.011	<20	0.99	0.010	0.28	<0.1	0.15	7.1	0.1	<0.05	3	<0.5	<0.2
1418261	Rock	0.035	22	3	0.04	679	0.001	<20	0.45	0.048	0.23	<0.1	0.02	4.0	<0.1	<0.05	1	<0.5	0.4
DUP 1418261	QC	0.036	23	4	0.04	695	0.001	<20	0.50	0.053	0.26	<0.1	0.02	4.6	<0.1	<0.05	1	<0.5	0.3
1418312	Rock	0.025	25	6	0.09	1291	0.001	<20	0.29	0.045	0.13	<0.1	0.09	3.2	<0.1	0.08	<1	<0.5	<0.2
DUP 1418312	QC	0.022	22	7	0.08	997	0.001	<20	0.31	0.052	0.13	<0.1	0.08	2.7	<0.1	0.08	<1	<0.5	<0.2
1418346	Rock	0.015	6	8	0.06	1063	0.011	<20	0.42	0.020	0.18	<0.1	0.09	2.8	<0.1	<0.05	1	<0.5	0.3
DUP 1418346	QC	0.015	6	8	0.06	985	0.011	<20	0.41	0.018	0.17	<0.1	0.09	2.6	<0.1	<0.05	1	<0.5	0.4
Reference Materials																			
STD DS10	Standard	0.083	17	52	0.76	415	0.075	<20	1.01	0.066	0.33	2.7	0.24	2.7	4.6	0.27	5	1.6	4.6
STD DS10	Standard	0.078	17	54	0.79	421	0.073	<20	1.05	0.070	0.34	3.0	0.33	2.9	5.1	0.28	5	2.3	4.8



QUALITY CONTROL REPORT

WHI16000142.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			15.2	153.4	132.6	349	1.8	78.0	13.8	904	2.84	45.6	85.7	6.7	66	2.8	7.9	11.6	46	1.11
STD DS10	Standard			15.5	151.0	145.9	356	2.0	74.5	13.1	922	2.91	49.2	82.8	7.5	70	2.1	8.5	12.1	49	1.11
STD OREAS45EA	Standard			1.5	663.7	13.0	28	0.3	367.1	45.2	407	20.37	10.9	50.3	8.3	3	<0.1	0.3	0.2	295	0.03
STD OREAS45EA	Standard			1.4	687.7	12.8	30	0.2	400.3	50.7	432	20.66	11.5	62.5	8.5	3	<0.1	0.2	0.2	307	0.03
STD OREAS45EA	Standard			1.3	697.6	13.9	32	0.3	402.5	52.5	394	21.93	10.8	51.7	9.2	3	<0.1	0.3	0.2	316	0.03
STD OREAS45EA	Standard			1.7	726.6	15.2	34	0.3	396.7	51.2	421	21.18	12.3	51.0	9.8	3	<0.1	0.3	0.3	321	0.03
STD OXD108	Standard		0.421																		
STD OXD108	Standard		0.426																		
STD OXD108	Standard		0.406																		
STD OXI121	Standard		1.827																		
STD OXI121	Standard		1.812																		
STD OXI121	Standard		1.825																		
STD OXN117	Standard		7.735																		
STD OXN117	Standard		7.795																		
STD OXN117	Standard		7.608																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		



QUALITY CONTROL REPORT

WHI16000142.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.076	18	59	0.81	418	0.083	<20	1.08	0.074	0.35	3.1	0.28	2.9	5.2	0.30	5	2.0	5.0
STD DS10	Standard	0.080	20	60	0.80	456	0.090	<20	1.07	0.071	0.33	3.3	0.28	3.1	5.6	0.30	4	2.5	4.9
STD OREAS45EA	Standard	0.027	6	788	0.09	128	0.090	<20	3.13	0.018	0.05	<0.1	0.01	65.9	<0.1	<0.05	11	1.0	<0.2
STD OREAS45EA	Standard	0.029	6	897	0.09	136	0.086	<20	3.14	0.019	0.05	<0.1	0.01	74.2	<0.1	<0.05	12	1.0	<0.2
STD OREAS45EA	Standard	0.026	7	865	0.10	147	0.101	<20	3.36	0.024	0.06	<0.1	<0.01	74.8	<0.1	<0.05	14	1.1	<0.2
STD OREAS45EA	Standard	0.028	7	838	0.10	140	0.103	<20	3.28	0.025	0.06	<0.1	<0.01	73.7	<0.1	<0.05	14	1.4	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000142.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
BLK	Blank	<0.005																				
Prep Wash																						
ROCK-WHI	Prep Blank	<0.005	0.5	4.2	2.3	38	<0.1	1.4	3.7	425	1.75	0.9	<0.5	2.1	27	<0.1	<0.1	<0.1	23	0.66		
ROCK-WHI	Prep Blank	<0.005	0.7	3.3	1.5	32	<0.1	0.7	3.6	427	1.74	1.0	1.0	2.1	26	<0.1	<0.1	<0.1	23	0.63		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 11, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000142.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2		
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.042	5	3	0.40	75	0.084	<20	1.00	0.110	0.10	0.1	0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.041	5	2	0.40	72	0.083	<20	0.99	0.103	0.10	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 02, 2016
Report Date: August 17, 2016
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI16000143.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV-2016-07-26-Rock-GTP
P.O. Number
Number of Samples: 42

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.


Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1
CANADA

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	42	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	42	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	42	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	42	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS


JEFFREY CANNON
Geochemistry Department Supervisor

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 2 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000143.1

Method Analyte	Unit	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
MDL		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	0.1	0.1	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1418378	Rock	1.49	0.030	0.9	76.5	42.7	90	1.1	5.7	14.6	1341	4.79	3.1	31.0	2.6	17	<0.1	0.3	0.5	49	0.21	
1338746	Rock	1.09	0.344	2.3	28.2	4.5	53	1.0	9.4	8.2	483	2.57	5.0	659.6	4.4	91	0.2	3.5	0.1	26	2.05	
1338747	Rock	0.89	0.149	2.2	12.3	3.1	60	0.3	10.3	10.6	685	3.46	2.2	141.0	5.0	49	0.1	0.9	0.1	47	1.09	
1338748	Rock	1.06	0.323	4.8	15.9	26.4	121	1.0	11.6	13.0	791	3.51	3.7	331.7	5.1	81	0.4	1.5	0.5	44	0.37	
1338749	Rock	0.75	0.293	2.6	23.3	10.1	83	0.6	9.8	11.0	628	3.17	5.9	270.8	4.0	66	0.3	1.7	0.1	37	0.26	
1338750	Rock	1.08	0.106	2.2	14.1	27.8	55	0.2	9.3	8.4	681	2.23	3.6	192.3	9.7	69	0.2	1.3	0.3	33	0.85	
1345976	Rock	1.71	0.006	1.2	11.1	6.5	30	<0.1	2.7	3.0	379	1.89	1.5	2.7	16.2	51	<0.1	0.3	0.4	8	0.53	
1345977	Rock	1.07	0.006	2.3	13.2	7.0	32	<0.1	3.3	3.6	402	2.02	1.8	2.9	16.5	62	<0.1	0.6	0.4	9	0.38	
1345978	Rock	1.43	<0.005	1.8	13.4	5.5	31	<0.1	18.4	8.4	496	2.51	12.0	2.8	12.9	67	<0.1	0.9	0.6	20	0.69	
1345979	Rock	1.07	<0.005	1.4	10.8	10.5	32	<0.1	5.7	4.3	393	2.00	6.3	2.1	15.6	55	0.1	0.4	0.7	12	0.37	
1345980	Rock	1.20	<0.005	1.7	20.7	8.8	37	<0.1	7.2	4.3	381	2.40	8.1	4.4	16.8	99	0.2	0.5	0.7	16	2.47	
1345981	Rock	1.11	<0.005	1.2	16.3	8.2	35	<0.1	6.3	4.7	410	2.08	2.6	3.2	17.6	64	<0.1	0.5	0.4	15	0.74	
1345982	Rock	1.42	<0.005	1.4	7.9	10.5	30	<0.1	5.4	4.8	452	2.26	3.4	1.2	7.0	80	<0.1	0.7	0.4	10	1.22	
1345983	Rock	0.96	<0.005	1.4	5.9	5.7	26	<0.1	6.8	4.6	336	1.71	2.1	1.7	13.7	80	<0.1	0.5	0.1	16	1.89	
1345984	Rock	1.55	0.042	2.1	16.0	10.7	30	<0.1	3.0	4.0	598	2.04	2.1	19.2	17.1	56	<0.1	0.9	0.2	8	0.61	
1345985	Rock	1.25	0.011	2.0	19.8	10.2	33	<0.1	6.6	5.4	485	2.19	2.7	11.0	12.2	50	<0.1	1.0	0.5	14	0.32	
1345986	Rock	0.75	0.014	2.0	13.2	12.0	39	<0.1	5.0	5.4	433	2.40	9.2	11.8	10.4	89	<0.1	0.7	<0.1	9	0.48	
1345987	Rock	0.84	0.025	1.9	11.8	6.3	33	<0.1	10.7	8.3	753	2.64	4.4	19.2	11.4	59	<0.1	0.5	0.1	24	0.24	
1345988	Rock	1.26	0.018	1.7	5.9	6.9	13	<0.1	2.5	2.6	351	1.27	13.0	12.9	4.1	42	<0.1	0.3	0.2	6	0.13	
1345989	Rock	0.98	0.015	1.8	5.9	5.9	17	<0.1	2.5	2.1	333	1.45	3.8	13.7	10.8	65	<0.1	0.4	<0.1	7	0.10	
1345990	Rock	1.07	0.036	2.8	11.1	9.0	24	<0.1	2.9	2.7	429	1.74	4.7	24.2	12.0	50	<0.1	1.0	0.2	10	0.11	
1345991	Rock	1.51	0.018	2.6	8.9	8.6	33	<0.1	3.6	3.0	478	1.72	2.8	12.6	15.0	60	<0.1	1.4	0.2	10	0.30	
1345992	Rock	1.33	0.028	5.2	11.1	6.3	14	<0.1	7.4	3.0	383	1.73	9.0	30.2	19.8	89	<0.1	2.3	0.2	7	0.11	
1345993	Rock	1.17	0.229	6.4	12.5	7.4	18	<0.1	28.6	7.8	670	2.63	41.7	114.0	14.8	157	0.1	3.5	0.2	19	0.44	
1345994	Rock	0.92	0.447	9.9	12.1	6.1	37	0.4	28.7	9.2	940	3.03	19.7	1804.6	8.2	81	0.2	3.4	0.2	32	0.29	
1345995	Rock	1.14	0.324	5.3	39.5	13.2	33	0.3	34.0	12.7	660	2.43	47.7	237.6	11.5	108	0.2	8.8	0.2	22	0.95	
1345996	Rock	0.70	2.183	9.5	73.3	12.2	90	0.6	123.3	23.8	860	4.95	85.8	1872.3	14.0	89	0.3	6.8	0.2	53	0.76	
1345997	Rock	1.13	1.544	8.1	54.2	14.7	69	0.9	111.6	21.4	1075	3.84	44.3	1019.8	30.9	135	0.3	4.5	0.2	38	0.24	
1345998	Rock	1.38	0.018	4.3	16.4	8.7	50	<0.1	67.9	14.9	492	3.20	32.2	16.8	23.4	53	0.2	1.3	0.2	42	0.19	
1418353	Rock	1.55	<0.005	0.9	13.1	4.1	50	<0.1	23.0	15.4	668	3.31	1.2	1.7	8.8	21	<0.1	0.1	0.2	41	0.71	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 2 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000143.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
	MDL	%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
1418378	Rock	0.064	16	4	0.33	192	0.009	<20	0.82	0.026	0.16	0.2	0.04	16.3	<0.1	<0.05	4	0.9	0.6
1338746	Rock	0.009	12	7	0.11	1077	0.001	<20	0.34	0.042	0.15	<0.1	0.31	9.9	<0.1	<0.05	<1	<0.5	0.7
1338747	Rock	0.042	9	22	0.37	760	0.026	<20	0.93	0.016	0.54	<0.1	0.11	12.8	0.2	<0.05	3	<0.5	0.2
1338748	Rock	0.032	14	15	0.11	1922	0.004	<20	0.53	0.030	0.18	<0.1	0.18	15.6	<0.1	<0.05	2	0.8	0.7
1338749	Rock	0.029	10	9	0.08	1600	0.002	<20	0.45	0.026	0.17	<0.1	0.16	11.7	<0.1	<0.05	2	<0.5	0.5
1338750	Rock	0.046	20	13	0.25	1409	0.029	<20	0.55	0.046	0.25	0.1	0.07	8.9	<0.1	<0.05	3	<0.5	<0.2
1345976	Rock	0.025	32	5	0.16	1115	0.029	<20	0.58	0.041	0.27	0.1	0.17	2.9	0.1	<0.05	3	<0.5	<0.2
1345977	Rock	0.031	39	4	0.25	711	0.023	<20	0.68	0.038	0.24	<0.1	0.25	3.5	0.1	<0.05	4	0.5	<0.2
1345978	Rock	0.017	24	16	0.17	1926	0.006	<20	0.50	0.030	0.26	0.2	0.55	6.9	0.1	<0.05	2	<0.5	<0.2
1345979	Rock	0.021	34	7	0.20	1079	0.029	<20	0.57	0.039	0.29	0.1	0.45	4.0	0.2	<0.05	3	<0.5	0.3
1345980	Rock	0.035	34	8	0.32	626	0.034	<20	0.67	0.034	0.27	0.1	0.27	4.2	0.2	0.07	3	0.6	0.2
1345981	Rock	0.031	43	10	0.35	758	0.037	<20	0.70	0.038	0.31	0.1	0.17	4.2	0.2	<0.05	4	<0.5	<0.2
1345982	Rock	0.017	9	6	0.07	614	0.001	<20	0.39	0.026	0.18	<0.1	0.40	5.7	<0.1	<0.05	2	<0.5	<0.2
1345983	Rock	0.018	25	8	0.09	1187	0.003	<20	0.38	0.038	0.17	<0.1	0.24	4.3	<0.1	<0.05	2	<0.5	<0.2
1345984	Rock	0.020	26	4	0.06	1141	0.003	<20	0.46	0.022	0.21	<0.1	0.26	3.2	<0.1	<0.05	2	<0.5	<0.2
1345985	Rock	0.024	21	8	0.12	933	0.006	<20	0.63	0.023	0.25	<0.1	0.29	5.4	0.1	<0.05	2	<0.5	<0.2
1345986	Rock	0.043	18	4	0.06	2563	0.001	<20	0.45	0.018	0.19	<0.1	0.28	5.1	<0.1	0.06	2	<0.5	<0.2
1345987	Rock	0.035	19	13	0.18	1055	0.009	<20	0.88	0.020	0.32	<0.1	0.08	8.0	0.1	<0.05	3	<0.5	<0.2
1345988	Rock	0.007	11	3	0.07	1007	0.001	<20	0.54	0.006	0.18	0.3	0.11	2.5	<0.1	<0.05	1	<0.5	<0.2
1345989	Rock	0.023	24	4	0.04	2179	0.002	<20	0.42	0.026	0.15	<0.1	0.13	2.5	<0.1	<0.05	1	<0.5	<0.2
1345990	Rock	0.015	29	4	0.06	1176	0.002	<20	0.59	0.021	0.16	<0.1	0.12	3.3	<0.1	<0.05	2	<0.5	<0.2
1345991	Rock	0.022	26	4	0.03	1537	0.002	<20	0.33	0.033	0.16	<0.1	0.13	1.6	<0.1	<0.05	1	<0.5	<0.2
1345992	Rock	0.009	26	5	0.04	3254	<0.001	<20	0.37	0.006	0.16	0.2	0.35	1.4	<0.1	0.08	1	<0.5	<0.2
1345993	Rock	0.021	24	5	0.09	4087	<0.001	<20	0.46	0.006	0.19	0.3	0.47	2.3	0.1	0.09	1	<0.5	<0.2
1345994	Rock	0.056	21	8	0.09	1402	0.003	<20	0.53	0.008	0.17	0.3	0.66	10.6	0.1	<0.05	2	<0.5	<0.2
1345995	Rock	0.044	19	13	0.06	1476	0.002	<20	0.38	0.008	0.24	0.2	0.28	6.9	0.1	<0.05	1	<0.5	<0.2
1345996	Rock	0.107	14	50	0.19	171	0.007	<20	0.64	0.007	0.29	0.1	0.29	15.2	0.2	<0.05	3	<0.5	1.3
1345997	Rock	0.043	25	49	0.28	2207	0.010	<20	0.83	0.020	0.30	<0.1	0.88	12.3	0.2	<0.05	3	<0.5	0.9
1345998	Rock	0.041	19	75	0.27	353	0.013	<20	0.79	0.023	0.35	0.1	0.27	9.5	0.2	<0.05	3	<0.5	<0.2
1418353	Rock	0.036	17	42	0.36	394	0.031	<20	0.94	0.017	0.49	<0.1	0.08	11.1	0.2	<0.05	3	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 3 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000143.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		MDL	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1418354	Rock	1.31	<0.005	0.7	26.2	7.1	34	<0.1	10.4	8.4	378	1.43	1.1	<0.5	5.0	20	<0.1	<0.1	0.1	8	1.48
1418355	Rock	1.63	<0.005	1.1	34.4	8.7	86	<0.1	35.2	22.6	535	4.36	1.5	0.6	18.7	19	<0.1	<0.1	0.6	20	0.14
1418356	Rock	1.28	<0.005	2.7	44.0	38.4	74	0.1	15.1	8.7	656	2.04	39.0	<0.5	3.2	644	1.0	1.4	0.1	16	19.39
1418357	Rock	1.31	<0.005	1.2	26.3	3.5	54	<0.1	21.7	12.9	482	2.73	2.0	<0.5	11.7	68	<0.1	0.3	0.2	16	2.83
1418358	Rock	1.53	<0.005	1.4	55.2	17.8	142	0.1	24.0	15.9	523	3.50	15.0	<0.5	10.4	109	3.1	0.5	0.7	24	4.34
1418359	Rock	1.41	<0.005	1.1	39.5	6.6	91	<0.1	23.8	16.0	410	3.24	6.8	<0.5	9.5	54	0.1	0.2	0.3	16	2.17
1418360	Rock	1.40	<0.005	1.8	38.5	16.5	68	0.1	22.4	11.8	567	2.46	22.3	<0.5	5.9	244	0.5	0.4	0.3	21	14.10
1418361	Rock	1.50	<0.005	6.4	47.7	16.9	36	<0.1	15.8	7.6	321	1.54	30.7	<0.5	2.5	627	0.4	0.3	0.1	13	15.20
1418362	Rock	0.76	<0.005	1.8	40.1	8.8	51	<0.1	21.2	13.1	373	2.63	11.4	1.6	3.6	204	0.1	0.5	0.3	38	6.53
1418363	Rock	1.28	<0.005	0.6	65.6	5.4	79	<0.1	20.8	10.5	391	2.57	9.0	<0.5	11.5	106	0.4	0.2	0.3	21	2.69
1418364	Rock	1.50	<0.005	0.4	18.1	2.5	37	<0.1	17.8	10.7	356	2.36	2.9	<0.5	7.8	52	<0.1	0.1	0.1	10	1.50
1418365	Rock	1.62	<0.005	0.5	32.8	1.8	40	<0.1	21.5	12.1	361	2.76	5.0	<0.5	10.1	44	<0.1	0.2	0.1	11	1.07



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000143.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1418354	Rock	0.008	10	8	0.05	155	<0.001	<20	0.32	0.040	0.12	<0.1	0.01	2.7	<0.1	<0.05	1	<0.5	<0.2
1418355	Rock	0.031	27	18	0.35	451	0.055	<20	1.00	0.017	0.62	<0.1	0.02	4.3	0.2	<0.05	4	<0.5	<0.2
1418356	Rock	0.065	8	7	0.26	286	<0.001	<20	0.35	0.017	0.15	<0.1	0.24	6.0	<0.1	<0.05	<1	0.8	<0.2
1418357	Rock	0.042	25	12	0.15	471	0.004	<20	0.50	0.027	0.30	<0.1	0.05	4.3	0.1	<0.05	2	<0.5	<0.2
1418358	Rock	0.027	16	15	0.08	472	<0.001	<20	0.40	0.024	0.19	<0.1	0.61	7.7	<0.1	<0.05	1	<0.5	<0.2
1418359	Rock	0.016	16	13	0.17	519	0.001	<20	0.49	0.017	0.24	<0.1	0.14	4.8	<0.1	<0.05	1	<0.5	<0.2
1418360	Rock	0.048	11	12	0.33	202	<0.001	<20	0.33	0.022	0.12	<0.1	0.53	8.1	<0.1	<0.05	<1	1.0	<0.2
1418361	Rock	0.029	6	7	0.21	362	<0.001	<20	0.29	0.022	0.10	<0.1	0.29	4.2	<0.1	<0.05	<1	<0.5	<0.2
1418362	Rock	0.019	8	13	0.34	402	0.007	<20	0.73	0.030	0.11	<0.1	0.13	4.7	<0.1	<0.05	2	<0.5	<0.2
1418363	Rock	0.015	17	12	0.17	677	0.001	<20	0.40	0.032	0.19	<0.1	0.24	6.7	<0.1	<0.05	1	<0.5	<0.2
1418364	Rock	0.030	12	9	0.46	676	0.002	<20	0.38	0.025	0.24	<0.1	0.30	2.6	<0.1	<0.05	<1	<0.5	<0.2
1418365	Rock	0.031	14	8	0.24	466	0.001	<20	0.40	0.025	0.26	<0.1	0.96	2.5	<0.1	<0.05	1	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000143.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1345981	Rock	1.11	<0.005	1.2	16.3	8.2	35	<0.1	6.3	4.7	410	2.08	2.6	3.2	17.6	64	<0.1	0.5	0.4	15	0.74
REP 1345981	QC		0.006																		
1345995	Rock	1.14	0.324	5.3	39.5	13.2	33	0.3	34.0	12.7	660	2.43	47.7	237.6	11.5	108	0.2	8.8	0.2	22	0.95
REP 1345995	QC			5.2	37.7	12.4	32	0.3	32.8	11.7	625	2.37	46.7	402.5	10.5	108	0.2	8.2	0.2	21	0.91
1345996	Rock	0.70	2.183	9.5	73.3	12.2	90	0.6	123.3	23.8	860	4.95	85.8	1872.3	14.0	89	0.3	6.8	0.2	53	0.76
REP 1345996	QC		2.051																		
1418358	Rock	1.53	<0.005	1.4	55.2	17.8	142	0.1	24.0	15.9	523	3.50	15.0	<0.5	10.4	109	3.1	0.5	0.7	24	4.34
REP 1418358	QC		<0.005																		
Core Reject Duplicates																					
1345989	Rock	0.98	0.015	1.8	5.9	5.9	17	<0.1	2.5	2.1	333	1.45	3.8	13.7	10.8	65	<0.1	0.4	<0.1	7	0.10
DUP 1345989	QC		0.016	1.8	6.6	5.9	17	<0.1	2.7	2.3	335	1.46	4.0	13.7	11.0	65	<0.1	0.5	<0.1	7	0.10
Reference Materials																					
STD DS10	Standard			13.4	155.9	140.7	352	1.8	72.8	13.7	882	2.69	46.1	129.4	7.2	67	2.9	8.8	13.2	40	1.03
STD DS10	Standard			14.5	167.3	153.5	372	2.1	76.7	13.8	918	2.82	46.7	64.4	8.2	70	2.9	8.9	13.3	42	1.10
STD OREAS45EA	Standard			1.7	670.8	14.4	31	0.3	362.9	52.8	418	21.31	11.6	54.2	9.9	4	<0.1	0.4	0.3	305	0.03
STD OREAS45EA	Standard			1.5	696.5	14.9	32	0.3	384.2	54.2	420	21.44	11.4	58.1	10.4	4	<0.1	0.3	0.3	314	0.03
STD OXD108	Standard		0.416																		
STD OXD108	Standard		0.416																		
STD OXD108	Standard		0.424																		
STD OXI121	Standard		1.786																		
STD OXI121	Standard		1.902																		
STD OXI121	Standard		1.786																		
STD OXN117	Standard		7.616																		
STD OXN117	Standard		7.753																		
STD OXN117	Standard		7.737																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		



QUALITY CONTROL REPORT

WHI16000143.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1345981	Rock	0.031	43	10	0.35	758	0.037	<20	0.70	0.038	0.31	0.1	0.17	4.2	0.2	<0.05	4	<0.5	<0.2
REP 1345981	QC																		
1345995	Rock	0.044	19	13	0.06	1476	0.002	<20	0.38	0.008	0.24	0.2	0.28	6.9	0.1	<0.05	1	<0.5	<0.2
REP 1345995	QC	0.041	18	12	0.06	1427	0.002	<20	0.37	0.007	0.23	0.2	0.27	6.3	0.1	<0.05	1	<0.5	0.2
1345996	Rock	0.107	14	50	0.19	171	0.007	<20	0.64	0.007	0.29	0.1	0.29	15.2	0.2	<0.05	3	<0.5	1.3
REP 1345996	QC																		
1418358	Rock	0.027	16	15	0.08	472	<0.001	<20	0.40	0.024	0.19	<0.1	0.61	7.7	<0.1	<0.05	1	<0.5	<0.2
REP 1418358	QC																		
Core Reject Duplicates																			
1345989	Rock	0.023	24	4	0.04	2179	0.002	<20	0.42	0.026	0.15	<0.1	0.13	2.5	<0.1	<0.05	1	<0.5	<0.2
DUP 1345989	QC	0.022	23	4	0.04	2238	0.002	<20	0.41	0.025	0.15	0.1	0.15	2.5	<0.1	<0.05	1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.072	17	54	0.77	394	0.080	<20	1.00	0.066	0.33	3.5	0.26	2.8	4.9	0.27	4	2.5	4.9
STD DS10	Standard	0.077	19	55	0.79	408	0.085	<20	1.07	0.070	0.35	3.6	0.28	3.0	5.2	0.28	4	2.2	4.9
STD OREAS45EA	Standard	0.027	7	777	0.09	150	0.098	<20	3.08	0.019	0.05	<0.1	0.01	75.5	<0.1	<0.05	12	1.2	<0.2
STD OREAS45EA	Standard	0.027	7	803	0.09	152	0.102	<20	3.18	0.019	0.05	<0.1	0.01	78.4	<0.1	<0.05	13	0.9	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000143.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OXN117 Expected		7.679																			
STD OXI121 Expected		1.834																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.7	4.7	1.5	31	<0.1	1.5	4.2	424	1.80	0.9	0.9	2.6	31	<0.1	<0.1	<0.1	23	0.62	
ROCK-WHI	Prep Blank	<0.005	0.6	3.8	1.5	32	<0.1	1.6	4.0	439	1.85	0.9	<0.5	2.9	31	<0.1	<0.1	<0.1	23	0.68	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver BC V6C 1E1 CANADA

Project: QV
Report Date: August 17, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000143.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXN117 Expected																				
STD OXI121 Expected																				
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.040	6	4	0.42	86	0.093	<20	0.98	0.100	0.09	0.1	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.044	6	4	0.41	79	0.094	<20	1.05	0.109	0.11	0.1	<0.01	3.0	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: August 23, 2016
Report Date: September 13, 2016
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI16000210.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV2016-08-19Rock
P.O. Number
Number of Samples: 44

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	44	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	44	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	44	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	44	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 13, 2016

Page: 2 of 3 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000210.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419751	Rock	1.71	0.032	0.6	11.9	16.2	74	<0.1	5.0	7.8	736	2.87	30.3	31.6	17.9	20	0.1	0.1	0.2	28	0.26
1419752	Rock	0.93	0.007	0.3	4.4	19.5	68	<0.1	3.0	7.1	362	2.22	2.9	5.1	18.9	17	0.1	<0.1	<0.1	22	0.25
1419753	Rock	0.92	<0.005	0.5	3.4	3.7	103	<0.1	3.4	6.5	745	2.79	2.0	3.1	11.8	17	0.1	<0.1	<0.1	37	0.51
1419754	Rock	1.03	0.014	4.6	56.8	24.1	73	<0.1	7.3	9.5	1225	3.30	109.6	9.7	22.4	25	0.5	0.2	0.3	37	0.18
1419755	Rock	1.06	0.025	0.3	10.2	6.6	69	<0.1	4.3	8.6	452	3.11	4.1	22.9	14.5	16	<0.1	<0.1	<0.1	28	0.25
1419756	Rock	1.12	0.013	1.5	39.7	19.2	24	<0.1	3.1	3.4	1098	2.20	7.5	11.7	19.1	47	0.4	0.3	0.3	169	0.18
1419757	Rock	1.31	0.354	3.0	83.3	357.8	85	0.8	5.7	9.5	1004	2.88	44.8	196.4	16.9	23	0.9	0.2	2.9	60	0.16
1419758	Rock	1.18	0.024	0.6	22.8	30.9	62	<0.1	4.6	8.9	531	2.57	27.8	4.6	19.4	18	0.2	<0.1	0.3	37	0.20
1419759	Rock	1.31	<0.005	0.5	8.4	12.4	62	<0.1	4.2	8.0	508	2.43	2.7	2.9	18.6	30	<0.1	<0.1	<0.1	26	0.27
1419760	Rock	1.30	0.008	0.4	26.1	73.8	71	<0.1	5.0	7.6	512	3.01	3.7	4.1	20.8	24	0.2	0.1	0.3	38	0.24
1419761	Rock	1.18	<0.005	0.5	11.6	19.2	59	<0.1	4.7	6.7	471	2.33	3.0	5.5	17.7	43	0.2	<0.1	0.3	28	0.27
1419762	Rock	1.14	<0.005	0.5	16.8	26.2	61	<0.1	5.0	7.1	444	2.47	2.0	1.8	18.3	31	0.1	<0.1	0.3	27	0.30
1419763	Rock	0.80	0.006	1.6	23.5	20.2	54	<0.1	4.8	7.3	543	2.47	6.1	8.8	18.4	17	<0.1	<0.1	0.3	29	0.18
1419764	Rock	1.10	0.042	0.6	6.3	6.2	51	0.1	4.4	6.0	426	2.32	10.9	37.0	18.4	20	<0.1	<0.1	<0.1	21	0.18
1419765	Rock	1.22	0.357	1.0	11.5	81.9	84	0.9	3.7	4.5	252	2.29	189.4	371.2	15.9	33	0.3	0.2	0.2	11	0.06
1419766	Rock	1.15	0.019	0.4	11.9	38.0	56	0.2	4.3	7.7	909	2.46	33.2	16.0	17.9	21	0.4	<0.1	0.5	23	0.26
1419767	Rock	1.16	0.014	0.6	6.5	15.3	73	<0.1	5.1	7.8	524	2.85	4.2	12.9	18.0	20	0.2	0.1	0.2	29	0.26
1419768	Rock	1.07	0.007	0.4	8.7	47.9	53	<0.1	4.8	7.8	447	2.55	2.8	7.0	15.7	28	0.1	<0.1	0.2	28	0.28
1419769	Rock	1.08	0.015	0.4	22.4	38.8	69	<0.1	6.6	9.1	538	2.88	3.4	14.0	16.4	29	0.2	<0.1	0.4	32	0.30
1419770	Rock	1.77	0.015	0.4	20.4	77.3	67	0.2	8.8	8.2	700	2.80	6.0	14.1	15.4	41	0.5	0.1	1.0	42	0.31
1419771	Rock	1.06	0.006	0.3	10.9	60.3	56	<0.1	6.5	7.7	464	2.54	4.2	5.6	17.7	31	0.1	<0.1	0.6	33	0.29
1419772	Rock	0.66	0.058	0.7	15.6	73.7	47	0.2	8.1	8.6	311	2.38	14.3	47.2	13.2	28	<0.1	0.2	0.5	36	0.24
1419773	Rock	1.17	0.016	0.2	14.3	14.8	73	<0.1	5.8	8.0	797	2.99	4.2	10.5	17.4	25	0.1	<0.1	0.2	35	0.29
1419774	Rock	0.93	0.024	0.5	9.5	33.0	133	0.1	4.6	7.5	557	2.64	10.9	25.9	17.7	20	0.4	0.1	0.1	23	0.23
1419775	Rock	1.23	0.011	0.2	33.7	16.6	125	0.1	14.5	17.8	1310	4.65	4.4	11.4	12.1	33	0.5	0.1	0.2	95	0.50
1419776	Rock	1.55	0.011	0.5	23.7	51.1	75	<0.1	11.9	9.3	682	2.85	6.1	9.5	14.6	28	0.2	0.2	0.5	48	0.32
1419779	Rock	1.05	0.302	0.4	16.6	42.3	51	0.2	5.3	7.0	495	2.39	24.6	87.5	16.1	21	0.4	0.1	0.7	24	0.23
1419780	Rock	0.94	0.015	0.7	17.3	31.5	53	0.1	11.8	7.5	279	2.59	10.3	14.5	9.9	31	0.2	0.3	0.5	47	0.27
1419781	Rock	1.31	0.112	0.2	11.5	30.5	73	<0.1	5.0	8.4	615	2.84	3.5	10.7	14.5	26	0.3	<0.1	0.4	33	0.29
1419782	Rock	1.10	0.012	0.4	9.4	21.1	76	<0.1	5.7	9.1	758	3.24	2.6	11.2	18.8	28	0.1	<0.1	0.4	35	0.38



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 13, 2016

Page: 2 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000210.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419751	Rock	0.053	53	8	0.38	185	0.023	<20	1.31	0.034	0.39	<0.1	0.04	4.4	0.2	<0.05	7	<0.5	<0.2
1419752	Rock	0.056	50	6	0.25	152	0.016	<20	0.96	0.031	0.31	0.2	<0.01	4.3	0.1	<0.05	4	<0.5	<0.2
1419753	Rock	0.046	30	8	0.79	129	0.126	<20	1.20	0.057	0.57	<0.1	<0.01	6.8	0.1	<0.05	7	<0.5	<0.2
1419754	Rock	0.053	33	6	0.17	260	0.007	<20	0.72	0.016	0.34	<0.1	0.02	10.7	0.7	<0.05	4	0.5	<0.2
1419755	Rock	0.061	35	7	0.54	185	0.066	<20	1.37	0.035	0.63	<0.1	<0.01	3.8	0.3	<0.05	6	<0.5	<0.2
1419756	Rock	0.053	39	7	0.07	191	0.021	<20	0.43	0.024	0.25	0.4	<0.01	4.4	0.1	<0.05	2	<0.5	<0.2
1419757	Rock	0.056	22	5	0.08	182	0.009	<20	0.52	0.012	0.26	0.6	0.04	7.5	0.3	<0.05	3	0.7	1.2
1419758	Rock	0.061	55	9	0.47	119	0.053	<20	1.08	0.048	0.48	<0.1	<0.01	4.7	0.3	<0.05	6	<0.5	<0.2
1419759	Rock	0.050	41	8	0.44	121	0.056	<20	0.97	0.050	0.38	<0.1	<0.01	3.2	0.2	<0.05	5	<0.5	<0.2
1419760	Rock	0.063	48	9	0.40	177	0.029	<20	1.07	0.062	0.32	0.1	<0.01	5.8	0.1	<0.05	6	<0.5	<0.2
1419761	Rock	0.055	37	8	0.39	121	0.031	<20	1.04	0.051	0.34	<0.1	<0.01	4.0	0.2	<0.05	6	<0.5	<0.2
1419762	Rock	0.046	31	9	0.43	128	0.120	<20	1.14	0.064	0.54	0.2	<0.01	3.5	0.3	<0.05	6	<0.5	<0.2
1419763	Rock	0.050	53	8	0.34	169	0.045	<20	1.00	0.034	0.45	0.2	<0.01	4.8	0.3	<0.05	5	<0.5	<0.2
1419764	Rock	0.050	48	8	0.30	171	0.044	<20	1.02	0.036	0.47	0.1	0.02	3.4	0.3	<0.05	6	<0.5	<0.2
1419765	Rock	0.036	39	4	0.06	124	0.002	<20	0.53	0.007	0.24	<0.1	0.04	2.0	0.8	<0.05	2	<0.5	2.7
1419766	Rock	0.052	64	8	0.32	306	0.014	<20	1.11	0.028	0.36	0.1	0.02	4.3	0.3	<0.05	6	<0.5	<0.2
1419767	Rock	0.056	46	9	0.47	176	0.062	<20	1.24	0.033	0.50	0.1	<0.01	4.9	0.3	<0.05	7	<0.5	<0.2
1419768	Rock	0.051	26	9	0.46	186	0.079	<20	1.18	0.046	0.45	0.1	<0.01	3.3	0.2	<0.05	6	<0.5	<0.2
1419769	Rock	0.051	39	11	0.53	211	0.096	<20	1.28	0.041	0.55	<0.1	0.01	4.2	0.3	<0.05	7	<0.5	<0.2
1419770	Rock	0.057	52	22	0.51	213	0.049	<20	1.10	0.048	0.28	0.1	<0.01	5.8	0.2	<0.05	6	<0.5	<0.2
1419771	Rock	0.052	37	9	0.48	192	0.087	<20	1.09	0.048	0.49	<0.1	<0.01	4.0	0.3	<0.05	6	<0.5	<0.2
1419772	Rock	0.035	43	15	0.36	207	0.074	<20	1.14	0.038	0.32	0.1	0.02	4.3	0.2	<0.05	5	<0.5	0.4
1419773	Rock	0.064	51	12	0.58	244	0.053	<20	1.30	0.036	0.39	0.1	0.02	5.8	0.2	<0.05	8	<0.5	<0.2
1419774	Rock	0.051	55	7	0.36	300	0.039	<20	1.27	0.019	0.55	0.1	0.02	3.6	0.3	<0.05	6	<0.5	<0.2
1419775	Rock	0.109	51	26	1.20	344	0.057	<20	1.91	0.033	0.35	0.1	0.01	11.6	0.1	<0.05	11	<0.5	<0.2
1419776	Rock	0.058	43	40	0.59	236	0.087	<20	1.34	0.036	0.43	0.1	0.01	5.9	0.2	<0.05	7	<0.5	<0.2
1419779	Rock	0.050	47	9	0.27	180	0.029	<20	0.92	0.021	0.31	0.3	0.02	4.2	0.2	<0.05	4	<0.5	0.5
1419780	Rock	0.039	36	24	0.41	241	0.068	<20	1.43	0.036	0.15	0.2	0.02	5.0	0.1	<0.05	5	<0.5	<0.2
1419781	Rock	0.059	31	11	0.53	190	0.094	<20	1.23	0.043	0.54	<0.1	<0.01	3.5	0.3	<0.05	6	<0.5	<0.2
1419782	Rock	0.078	45	11	0.68	193	0.123	<20	1.50	0.038	0.74	0.1	<0.01	4.0	0.4	<0.05	7	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 13, 2016

Page: 3 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000210.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419783	Rock	1.09	0.008	0.4	13.3	21.0	70	<0.1	5.6	8.0	469	2.87	3.2	5.9	16.5	23	0.3	0.1	0.3	31	0.31
1419784	Rock	1.43	0.035	0.4	15.4	70.7	58	<0.1	6.5	7.6	553	2.61	4.1	12.8	13.8	24	0.2	0.1	0.9	33	0.30
1418379	Rock	1.36	0.033	0.4	26.1	189.2	54	1.1	3.4	5.3	1079	2.55	1.1	16.4	3.7	26	0.3	0.1	1.8	26	0.12
1418380	Rock	1.91	0.094	0.9	20.2	24.5	59	1.8	2.4	3.4	654	2.00	2.4	88.2	3.6	28	0.5	0.2	0.3	16	0.18
1418381	Rock	1.36	0.121	10.8	127.2	112.3	83	5.7	10.8	14.5	1186	3.46	31.4	115.0	1.0	54	0.6	7.4	1.7	33	1.82
1418382	Rock	1.17	0.048	2.8	105.3	9.2	77	0.6	3.7	10.2	729	4.34	9.3	42.4	2.1	32	0.2	1.8	0.3	39	0.10
1418383	Rock	1.52	0.119	1.3	24.8	11.6	57	2.4	4.9	5.6	380	2.83	20.0	110.4	5.3	37	<0.1	1.5	0.1	14	0.06
1418384	Rock	1.30	0.082	3.3	22.4	6.6	22	0.8	1.3	1.5	44	1.01	8.6	74.3	1.1	37	<0.1	1.9	0.2	4	0.02
1418385	Rock	1.20	0.262	2.2	15.0	9.9	37	0.8	3.4	4.3	486	1.89	9.3	288.2	6.3	37	0.1	0.3	0.1	8	0.03
1418386	Rock	1.43	0.102	4.3	32.4	11.3	23	1.3	7.8	8.7	533	2.68	10.3	89.1	6.5	25	0.1	0.4	0.3	18	0.13
1418387	Rock	1.17	0.121	1.4	21.1	12.8	34	0.9	3.8	6.0	490	2.08	5.5	110.6	8.4	27	<0.1	0.1	0.2	15	0.68
1418388	Rock	1.56	0.253	1.7	27.9	11.9	27	2.1	2.9	7.3	540	2.32	6.4	230.0	6.6	35	0.1	0.2	0.2	13	0.61
1419777	Rock	1.06	0.009	0.4	11.4	32.2	87	<0.1	6.4	8.3	623	2.75	4.7	5.2	18.5	28	0.4	<0.1	0.4	34	0.30
1419778	Rock	1.55	0.013	0.4	16.6	33.9	68	<0.1	5.4	7.2	680	2.78	2.8	9.8	17.9	21	0.2	<0.1	0.7	39	0.24



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: September 13, 2016

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000210.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1419783	Rock	0.065	37	11	0.49	174	0.085	<20	1.31	0.034	0.57	<0.1	<0.01	3.9	0.3	<0.05	7	<0.5	<0.2
1419784	Rock	0.056	34	10	0.46	190	0.072	<20	1.25	0.035	0.51	0.2	0.01	3.5	0.3	<0.05	6	<0.5	<0.2
1418379	Rock	0.031	14	5	0.06	426	0.006	<20	0.39	0.040	0.12	0.2	0.04	8.3	<0.1	<0.05	1	<0.5	<0.2
1418380	Rock	0.031	16	3	0.05	196	0.001	<20	0.37	0.038	0.15	<0.1	0.06	6.0	<0.1	<0.05	2	<0.5	0.6
1418381	Rock	0.018	6	7	0.09	417	0.001	<20	0.46	0.006	0.25	<0.1	0.11	17.2	<0.1	0.06	2	0.9	2.5
1418382	Rock	0.055	10	3	0.10	200	0.003	<20	0.55	0.016	0.22	<0.1	0.12	13.6	<0.1	0.07	2	0.7	0.9
1418383	Rock	0.056	20	4	0.03	570	<0.001	<20	0.35	0.004	0.25	0.1	0.15	6.5	<0.1	0.06	<1	1.2	3.1
1418384	Rock	0.014	3	3	<0.01	589	<0.001	<20	0.31	0.007	0.30	<0.1	<0.01	2.1	<0.1	0.24	<1	0.6	0.8
1418385	Rock	0.026	21	4	0.02	222	0.002	<20	0.32	0.007	0.29	<0.1	0.01	3.3	<0.1	0.15	<1	0.7	1.2
1418386	Rock	0.060	20	6	0.03	119	0.001	<20	0.35	0.009	0.24	<0.1	0.02	7.9	<0.1	<0.05	<1	<0.5	1.4
1418387	Rock	0.042	22	7	0.06	119	0.002	<20	0.45	0.022	0.29	<0.1	0.03	4.9	<0.1	<0.05	1	<0.5	1.1
1418388	Rock	0.050	21	4	0.04	316	0.001	<20	0.33	0.007	0.25	<0.1	0.05	7.5	<0.1	<0.05	1	<0.5	2.1
1419777	Rock	0.054	37	12	0.57	180	0.091	<20	1.28	0.050	0.44	<0.1	<0.01	3.6	0.2	<0.05	7	<0.5	<0.2
1419778	Rock	0.055	44	10	0.53	165	0.089	<20	1.21	0.040	0.58	0.1	<0.01	4.6	0.2	<0.05	6	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000210.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1419779	Rock	1.05	0.302	0.4	16.6	42.3	51	0.2	5.3	7.0	495	2.39	24.6	87.5	16.1	21	0.4	0.1	0.7	24	0.23
REP 1419779	QC			0.4	17.1	45.0	55	0.2	5.5	7.7	508	2.45	26.1	109.9	17.6	22	0.4	0.1	0.8	24	0.23
1419778	Rock	1.55	0.013	0.4	16.6	33.9	68	<0.1	5.4	7.2	680	2.78	2.8	9.8	17.9	21	0.2	<0.1	0.7	39	0.24
REP 1419778	QC			0.3	16.9	33.3	67	<0.1	5.5	7.8	690	2.81	3.0	9.1	18.5	21	0.2	<0.1	0.6	39	0.25
Core Reject Duplicates																					
1419784	Rock	1.43	0.035	0.4	15.4	70.7	58	<0.1	6.5	7.6	553	2.61	4.1	12.8	13.8	24	0.2	0.1	0.9	33	0.30
DUP 1419784	QC		0.039	0.4	16.0	68.2	63	<0.1	6.0	7.6	550	2.65	4.0	17.5	13.4	26	0.2	0.1	0.9	33	0.30
Reference Materials																					
STD DS10	Standard			13.8	151.0	151.0	359	1.9	67.9	12.2	870	2.74	46.5	90.2	7.4	67	2.6	8.2	12.8	42	1.06
STD DS10	Standard			15.2	152.8	147.3	350	1.7	72.8	12.4	881	2.81	43.1	61.3	7.4	63	2.7	6.7	11.2	43	1.08
STD OREAS45EA	Standard			1.7	730.3	16.8	36	0.3	427.1	54.3	435	24.27	12.8	58.1	11.6	4	<0.1	0.3	0.3	323	0.03
STD OREAS45EA	Standard			1.6	711.2	15.7	33	0.3	403.9	53.1	416	22.22	11.0	53.9	11.0	4	<0.1	0.3	0.3	304	0.03
STD OXD108	Standard		0.410																		
STD OXI121	Standard		1.784																		
STD OXN117	Standard		7.473																		
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.8	3.8	2.2	30	<0.1	1.5	3.3	412	1.70	1.0	2.2	2.3	25	<0.1	<0.1	<0.1	23	0.56
ROCK-WHI	Prep Blank		<0.005	0.9	5.6	1.6	35	<0.1	1.4	3.7	429	1.82	1.2	1.3	2.6	31	<0.1	<0.1	<0.1	24	0.60



QUALITY CONTROL REPORT

WHI16000210.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1419779	Rock	0.050	47	9	0.27	180	0.029	<20	0.92	0.021	0.31	0.3	0.02	4.2	0.2	<0.05	4	<0.5	0.5
REP 1419779	QC	0.057	51	8	0.28	188	0.030	<20	0.93	0.023	0.32	0.3	0.02	4.2	0.2	<0.05	5	<0.5	0.7
1419778	Rock	0.055	44	10	0.53	165	0.089	<20	1.21	0.040	0.58	0.1	<0.01	4.6	0.2	<0.05	6	<0.5	<0.2
REP 1419778	QC	0.053	45	11	0.54	169	0.091	<20	1.23	0.040	0.58	0.2	0.01	4.4	0.2	<0.05	6	<0.5	<0.2
Core Reject Duplicates																			
1419784	Rock	0.056	34	10	0.46	190	0.072	<20	1.25	0.035	0.51	0.2	0.01	3.5	0.3	<0.05	6	<0.5	<0.2
DUP 1419784	QC	0.058	32	10	0.46	196	0.070	<20	1.23	0.038	0.51	0.1	<0.01	3.5	0.3	<0.05	6	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.078	18	55	0.78	434	0.079	<20	1.02	0.072	0.33	3.9	0.34	3.1	5.5	0.28	5	2.2	5.3
STD DS10	Standard	0.076	17	53	0.80	400	0.079	<20	1.05	0.074	0.34	3.6	0.25	2.8	4.8	0.29	4	2.1	4.9
STD OREAS45EA	Standard	0.032	9	908	0.10	173	0.106	<20	3.47	0.027	0.06	<0.1	0.01	83.3	<0.1	<0.05	14	0.9	<0.2
STD OREAS45EA	Standard	0.032	8	882	0.10	157	0.105	<20	3.32	0.024	0.06	<0.1	0.01	77.9	<0.1	<0.05	13	1.1	<0.2
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.045	5	6	0.39	75	0.087	<20	0.85	0.092	0.09	0.1	<0.01	2.5	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.045	6	4	0.40	77	0.095	<20	0.92	0.101	0.10	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2

Appendix D: RAB Drilling Samples

Sample ID	Hole ID	Project ID	Technician	Sample Type	Date	Time	From_ft	To_ft	From_m	To_m	Int_m	Recovery_liters	Sample Condition	Remarks	Duplicate of	Blank	Standard
1419001	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	10:58	0	5	0	1.524	1.524	12	Dry				
1419002	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	11:49	5	10	1.524	3.048	1.524	20	Dry				
1419003	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	11:59	10	15	3.048	4.572	1.524	18	Dry				
1419004	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:25	15	20	4.572	6.096	1.524	20	Dry				
1419005	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:30	20	25	6.096	7.62	1.524	20	Dry				
1419006	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:34	25	30	7.62	9.144	1.524	20	Dry				
1419007	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:38	30	35	9.144	10.668	1.524	20	Dry				
1419008	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:42	35	40	10.668	12.192	1.524	20	Dry				
1419009	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:47	40	45	12.192	13.716	1.524	20	Dry				
1419010	16QVV001	QVV	Corina Carlton CC02	Standard	2016-08-29	12:51			0	0	0			CDN-GS-1K			CDN-GS-1K
1419011	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:54	45	50	13.716	15.24	1.524	20	Dry				
1419012	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	12:56	50	55	15.24	16.764	1.524	20	Dry				
1419013	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	13:00	55	60	16.764	18.288	1.524	20	Dry				
1419014	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	13:05	60	65	18.288	19.812	1.524	20	Dry				
1419015	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	13:12	65	70	19.812	21.336	1.524	20	Dry				
1419016	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	13:16	70	75	21.336	22.86	1.524	20	Dry				
1419017	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:09	75	80	22.86	24.384	1.524	20	Dry				
1419018	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:16	80	85	24.384	25.908	1.524	20	Dry				
1419019	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:23	85	90	25.908	27.432	1.524	20	Dry				
1419020	16QVV001	QVV	Corina Carlton CC02	Blank	2016-08-29	14:28			0	0	0					Coarse Blank	
1419021	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:28	90	95	27.432	28.956	1.524	20	Dry				
1419022	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:33	95	100	28.956	30.48	1.524	20	Dry				
1419023	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:39	100	105	30.48	32.004	1.524	20	Dry				
1419024	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:46	105	110	32.004	33.528	1.524	20	Dry				
1419025	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	14:54	110	115	33.528	35.052	1.524	20	Dry				
1419026	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:04	115	120	35.052	36.576	1.524	20	Dry				
1419027	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:13	120	125	36.576	38.1	1.524	20	Dry				
1419028	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:23	125	130	38.1	39.624	1.524	20	Dry				
1419029	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:31	130	135	39.624	41.148	1.524	20	Dry				
1419030	16QVV001	QVV	Corina Carlton CC02	Duplicate	2016-08-29	15:42	130	135	39.624	41.148	1.524	20	Dry		1419029		
1419031	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:42	135	140	41.148	42.672	1.524	20	Dry				
1419032	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	15:52	140	145	42.672	44.196	1.524	20	Dry				
1419033	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:01	145	150	44.196	45.72	1.524	19	Dry				
1419034	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:10	150	155	45.72	47.244	1.524	20	Dry				
1419035	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:22	155	160	47.244	48.768	1.524	20	Dry				
1419036	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:32	160	165	48.768	50.292	1.524	20	Dry				
1419037	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:40	165	170	50.292	51.816	1.524	19	Dry				
1419038	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:50	170	175	51.816	53.34	1.524	19	Dry				
1419039	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	16:57	175	180	53.34	54.864	1.524	19	Dry				
1419040	16QVV001	QVV	Corina Carlton CC02	Standard	2016-08-29	17:04			0	0	0			CDN-ME-1205			CDN-ME-1205
1419041	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:05	180	185	54.864	56.388	1.524	19	Dry				
1419042	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:12	185	190	56.388	57.912	1.524	19	Dry				
1419043	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:22	190	195	57.912	59.436	1.524	19	Dry				
1419044	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:30	195	200	59.436	60.96	1.524	19	Dry				
1419045	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:41	200	205	60.96	62.484	1.524	19	Dry				
1419046	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	17:51	205	210	62.484	64.008	1.524	19	Dry				
1419047	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:00	210	215	64.008	65.532	1.524	19	Dry				
1419048	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:09	215	220	65.532	67.056	1.524	19	Dry				
1419049	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:16	220	225	67.056	68.58	1.524	19	Dry				
1419050	16QVV001	QVV	Corina Carlton CC02	Blank	2016-08-29	18:25			0	0	0					Coarse Blank	
1419051	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:26	225	230	68.58	70.104	1.524	19	Dry				
1419052	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:34	230	235	70.104	71.628	1.524	19	Dry				
1419053	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:46	235	240	71.628	73.152	1.524	19	Dry				
1419054	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	18:51	240	245	73.152	74.676	1.524	19	Dry				
1419055	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	19:00	245	250	74.676	76.2	1.524	19	Dry				
1419056	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-29	19:10	250	255	76.2	77.724	1.524	19	Dry				
1419057	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	09:07	255	260	77.724	79.248	1.524	19	Dry				
1419058	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	09:55	260	265	79.248	80.772	1.524	20	Dry				
1419059	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:03	265	270	80.772	82.296	1.524	20	Dry				
1419060	16QVV001	QVV	Corina Carlton CC02	Duplicate	2016-08-30	10:14	265	270	80.772	82.296	1.524	20	Dry		1419059		
1419061	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:14	270	275	82.296	83.82	1.524	20	Dry				
1419062	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:20	275	280	83.82	85.344	1.524	20	Dry				
1419063	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:28	280	285	85.344	86.868	1.524	20	Dry				

1419064	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:37	285	290	86.868	88.392	1.524	20	Dry				
1419065	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:46	290	295	88.392	89.916	1.524	20	Dry				
1419066	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	10:57	295	300	89.916	91.44	1.524	19	Dry				
1419067	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	11:06	300	305	91.44	92.964	1.524	10	Dry	Small sample, more brown than grey like prior samples, not as dusty but not damp			
1419068	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	11:15	305	310	92.964	94.488	1.524	8	Dry	Small sample			
1419069	16QVV001	QVV	Corina Carlton CC02	Sample	2016-08-30	11:54	310	315	94.488	96.012	1.524	2	Dry	Very small sample, entire sample put into analytical bag			
1419070	16QVV001	QVV	Corina Carlton CC02	Standard	2016-08-30	12:11			0	0	0			EOH			CDN-GS-1K
1419071	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	14:34	0	5	0	1.524	1.524	10	Dry				
1419072	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	14:46	5	10	1.524	3.048	1.524	25	Dry				
1419073	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	14:55	10	15	3.048	4.572	1.524	18	Dry				
1419074	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:10	15	20	4.572	6.096	1.524	20	Dry				
1419075	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:14	20	25	6.096	7.62	1.524	18	Dry				
1419076	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:19	25	30	7.62	9.144	1.524	18	Dry				
1419077	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:24	30	35	9.144	10.668	1.524	18	Dry				
1419078	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:29	35	40	10.668	12.192	1.524	18	Dry				
1419079	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:34	40	45	12.192	13.716	1.524	18	Dry				
1419080	16QVV002	QVV	Corina Carlton CC02	Blank	2016-08-30	15:40			0	0	0					Coarse Blank	
1419081	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:41	45	50	13.716	15.24	1.524	18	Dry				
1419082	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:46	50	55	15.24	16.764	1.524	18	Dry				
1419083	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:50	55	60	16.764	18.288	1.524	18	Dry				
1419084	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	15:54	60	65	18.288	19.812	1.524	18	Dry				
1419085	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:00	65	70	19.812	21.336	1.524	18	Dry				
1419086	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:06	70	75	21.336	22.86	1.524	18	Dry				
1419087	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:11	75	80	22.86	24.384	1.524	19	Dry				
1419088	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:16	80	85	24.384	25.908	1.524	18	Dry				
1419089	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:21	85	90	25.908	27.432	1.524	18	Dry				
1419090	16QVV002	QVV	Corina Carlton CC02	Duplicate	2016-08-30	16:30	85	90	25.908	27.432	1.524	18	Dry	1419089			
1419091	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:31	90	95	27.432	28.956	1.524	18	Dry				
1419092	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:34	95	100	28.956	30.48	1.524	18	Dry				
1419093	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:39	100	105	30.48	32.004	1.524	18	Dry				
1419094	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:45	105	110	32.004	33.528	1.524	18	Dry				
1419095	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:49	110	115	33.528	35.052	1.524	18	Dry				
1419096	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:54	115	120	35.052	36.576	1.524	18	Dry				
1419097	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	16:59	120	125	36.576	38.1	1.524	18	Dry				
1419098	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:04	125	130	38.1	39.624	1.524	20	Dry				
1419099	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:09	130	135	39.624	41.148	1.524	20	Dry				
1419100	16QVV002	QVV	Corina Carlton CC02	Standard	2016-08-30	17:13			0	0	0						CDN-ME-1205
1419101	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:13	135	140	41.148	42.672	1.524	20	Dry				
1419102	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:18	140	145	42.672	44.196	1.524	20	Dry				
1419103	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:22	145	150	44.196	45.72	1.524	18	Dry				
1419104	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:27	150	155	45.72	47.244	1.524	18	Dry				
1419105	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:32	155	160	47.244	48.768	1.524	20	Dry				
1419106	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:37	160	165	48.768	50.292	1.524	18	Dry				
1419107	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:42	165	170	50.292	51.816	1.524	18	Dry				
1419108	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:45	170	175	51.816	53.34	1.524	18	Dry				
1419109	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:49	175	180	53.34	54.864	1.524	18	Dry				
1419110	16QVV002	QVV	Corina Carlton CC02	Standard	2016-08-30	17:54			0	0	0						CDN-GS-1K
1419111	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:54	180	185	54.864	56.388	1.524	18	Dry				
1419112	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	17:59	185	190	56.388	57.912	1.524	18	Dry				
1419113	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:05	190	195	57.912	59.436	1.524	18	Dry				
1419114	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:10	195	200	59.436	60.96	1.524	18	Dry				
1419115	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:14	200	205	60.96	62.484	1.524	18	Dry				
1419116	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:19	205	210	62.484	64.008	1.524	18	Dry				
1419117	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:24	210	215	64.008	65.532	1.524	18	Dry				
1419118	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:28	215	220	65.532	67.056	1.524	18	Dry				
1419119	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:32	220	225	67.056	68.58	1.524	18	Dry				
1419120	16QVV002	QVV	Corina Carlton CC02	Blank	2016-08-30	18:38			0	0	0					Coarse Blank	
1419121	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:38	225	230	68.58	70.104	1.524	18	Dry				

1419122	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:42		230	235	70.104	71.628	1.524		18	Dry				
1419123	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:48		235	240	71.628	73.152	1.524		18	Dry				
1419124	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:53		240	245	73.152	74.676	1.524		18	Dry				
1419125	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	18:59		245	250	74.676	76.2	1.524		18	Dry				
1419126	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	19:05		250	255	76.2	77.724	1.524		18	Dry				
1419127	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	19:12		255	260	77.724	79.248	1.524		18	Dry				
1419128	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	19:56		260	265	79.248	80.772	1.524		18	Dry				
1419129	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-30	19:57		265	270	80.772	82.296	1.524		18	Dry				
1419130	16QVV002	QVV	Corina Carlton CC02	Duplicate	2016-08-30	19:57		265	270	80.772	82.296	1.524		18	Dry			1419129	
1419131	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	08:58		270	275	82.296	83.82	1.524		16	Dry				
1419132	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:14		275	280	83.82	85.344	1.524		20	Dry				
1419133	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:21		280	285	85.344	86.868	1.524		20	Dry				
1419134	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:27		285	290	86.868	88.392	1.524		20	Dry				
1419135	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:33		290	295	88.392	89.916	1.524		20	Dry				
1419136	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:38		295	300	89.916	91.44	1.524		20	Dry				
1419137	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:44		300	305	91.44	92.964	1.524		21	Dry				
1419138	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:50		305	310	92.964	94.488	1.524		20	Dry				
1419139	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	09:57		310	315	94.488	96.012	1.524		20	Dry				
1419140	16QVV002	QVV	Corina Carlton CC02	Standard	2016-08-31	10:03				0	0	0							CDN-ME-1205
1419141	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	10:03		315	320	96.012	97.536	1.524		20	Dry				
1419142	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	10:08		320	325	97.536	99.06	1.524		20	Dry				
1419143	16QVV002	QVV	Corina Carlton CC02	Sample	2016-08-31	10:15		325	330	99.06	100.584	1.524		20	Dry			EOH	
1419144	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	13:43		0	5	0	1.524	1.524		10	Dry				
1419145	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	13:59		5	10	1.524	3.048	1.524		18	Dry				
1419146	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	14:10		10	15	3.048	4.572	1.524		16	Dry				
1419147	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	14:27		15	20	4.572	6.096	1.524		24	Dry				
1419148	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:05		20	25	6.096	7.62	1.524		20	Dry				
1419149	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:21		25	30	7.62	9.144	1.524		20	Dry				
1419150	16QVV003	QVV	Corina Carlton CC02	Blank	2016-08-31	15:26				0	0	0							Coarse Blank
1419151	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:26		30	35	9.144	10.668	1.524		20	Dry				
1419152	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:31		35	40	10.668	12.192	1.524		18	Dry				
1419153	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:37		40	45	12.192	13.716	1.524		18	Dry				
1419154	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:42		45	50	13.716	15.24	1.524		18	Dry				
1419155	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:46		50	55	15.24	16.764	1.524		18	Dry				
1419156	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:49		55	60	16.764	18.288	1.524		18	Dry				
1419157	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:53		60	65	18.288	19.812	1.524		18	Dry				
1419158	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	15:58		65	70	19.812	21.336	1.524		18	Dry				
1419159	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:03		70	75	21.336	22.86	1.524		18	Dry				
1419160	16QVV003	QVV	Corina Carlton CC02	Duplicate	2016-08-31	16:10		70	75	21.336	22.86	1.524		18	Dry			1419159	
1419161	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:10		75	80	22.86	24.384	1.524		18	Dry				
1419162	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:15		80	85	24.384	25.908	1.524		18	Dry				
1419163	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:19		85	90	25.908	27.432	1.524		18	Dry				
1419164	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:24		90	95	27.432	28.956	1.524		18	Dry				
1419165	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:31		95	100	28.956	30.48	1.524		18	Dry				
1419166	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:38		100	105	30.48	32.004	1.524		18	Dry				
1419167	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:43		105	110	32.004	33.528	1.524		19	Dry				
1419168	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:49		110	115	33.528	35.052	1.524		19	Dry				
1419169	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	16:54		115	120	35.052	36.576	1.524		19	Dry				
1419170	16QVV003	QVV	Corina Carlton CC02	Standard	2016-08-31	17:01				0	0	0							CDN-GS-1K
1419171	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:01		120	125	36.576	38.1	1.524		19	Dry				
1419172	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:15		125	130	38.1	39.624	1.524		19	Dry				
1419173	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:22		130	135	39.624	41.148	1.524		19	Dry				
1419174	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:28		135	140	41.148	42.672	1.524		19	Dry				
1419175	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:36		140	145	42.672	44.196	1.524		19	Dry				
1419176	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:42		145	150	44.196	45.72	1.524		19	Dry				
1419177	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:48		150	155	45.72	47.244	1.524		19	Dry				
1419178	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	17:55		155	160	47.244	48.768	1.524		19	Dry				
1419179	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:03		160	165	48.768	50.292	1.524		19	Dry				
1419180	16QVV003	QVV	Corina Carlton CC02	Blank	2016-08-31	18:09				0	0	0							Coarse Blank
1419181	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:10		165	170	50.292	51.816	1.524		19	Dry				
1419182	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:15		170	175	51.816	53.34	1.524		19	Dry				
1419183	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:21		175	180	53.34	54.864	1.524		19	Dry				
1419184	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:27		180	185	54.864	56.388	1.524		19	Dry				
1419185	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:34		185	190	56.388	57.912	1.524		19	Dry				

1419186	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:40	190	195	57.912	59.436	1.524	19	Dry				
1419187	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:49	195	200	59.436	60.96	1.524	19	Dry				
1419188	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	18:55	200	205	60.96	62.484	1.524	19	Dry				
1419189	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	19:02	205	210	62.484	64.008	1.524	19	Dry				
1419190	16QVV003	QVV	Corina Carlton CC02	Duplicate	2016-08-31	19:12	205	210	62.484	64.008	1.524	19	Dry			1419189	
1419191	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	19:12	210	215	64.008	65.532	1.524	19	Dry				
1419192	16QVV003	QVV	Corina Carlton CC02	Sample	2016-08-31	19:17	215	220	65.532	67.056	1.524	19	Dry				
1419193	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	08:49	220	225	67.056	68.58	1.524	20	Dry				
1419194	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	09:16	225	230	68.58	70.104	1.524	21	Dry				
1419195	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	09:32	230	235	70.104	71.628	1.524	20	Dry				
1419196	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	09:40	235	240	71.628	73.152	1.524	20	Dry				
1419197	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	09:48	240	245	73.152	74.676	1.524	20	Dry				
1419198	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	09:56	245	250	74.676	76.2	1.524	20	Dry				
1419199	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:01	250	255	76.2	77.724	1.524	20	Dry				
1419200	16QVV003	QVV	Corina Carlton CC02	Standard	2016-09-01	10:07			0	0	0						CDN-ME-1205
1419201	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:07	255	260	77.724	79.248	1.524	20	Dry				
1419202	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:15	260	265	79.248	80.772	1.524	20	Dry				
1419203	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:22	265	270	80.772	82.296	1.524	20	Dry				
1419204	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:30	270	275	82.296	83.82	1.524	20	Dry				
1419205	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:36	275	280	83.82	85.344	1.524	20	Dry				
1419206	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	10:58	280	285	85.344	86.868	1.524	20	Dry				
1419207	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	11:07	285	290	86.868	88.392	1.524	20	Dry				
1419208	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	11:14	290	295	88.392	89.916	1.524	18	Dry				
1419209	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	12:24	295	300	89.916	91.44	1.524	20	Dry				
1419210	16QVV003	QVV	Corina Carlton CC02	Standard	2016-09-01	12:43			0	0	0						CDN-GS-1K
1419211	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	12:43	300	305	91.44	92.964	1.524	20	Dry				
1419212	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	12:54	305	310	92.964	94.488	1.524	20	Dry				
1419213	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	13:06	310	315	94.488	96.012	1.524	20	Dry				
1419214	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	13:16	315	320	96.012	97.536	1.524	20	Dry				
1419215	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	13:25	320	325	97.536	99.06	1.524	20	Dry				
1419216	16QVV003	QVV	Corina Carlton CC02	Sample	2016-09-01	13:35	325	330	99.06	100.584	1.524	20	Dry			EOH	
1162501	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-01	19:30	0	5	0	1.524	1.524	18	Dry				
1162502	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-01	19:42	5	10	1.524	3.048	1.524	22	Dry				
1162503	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	07:11	10	15	3.048	4.572	1.524	22	Dry				
1162504	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:23	15	20	4.572	6.096	1.524	30	Dry				
1162505	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:23	20	25	6.096	7.62	1.524	18	Dry				
1162506	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:43	25	30	7.62	9.144	1.524	20	Dry				
1162507	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:47	30	35	9.144	10.668	1.524	20	Dry				
1162508	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:52	35	40	10.668	12.192	1.524	18	Dry				
1162509	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	09:57	40	45	12.192	13.716	1.524	18	Dry				
1162510	16QVV004	QVV	Corina Carlton CC02	Standard	2016-09-02	10:03			0	0	0						CDN-GS-1K
1162511	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:03	45	50	13.716	15.24	1.524	19	Dry				
1162512	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:26	50	55	15.24	16.764	1.524	19	Dry				
1162513	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:30	55	60	16.764	18.288	1.524	18	Dry				
1162514	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:35	60	65	18.288	19.812	1.524	18	Dry				
1162515	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:41	65	70	19.812	21.336	1.524	18	Dry				
1162516	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:46	70	75	21.336	22.86	1.524	19	Dry				
1162517	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:52	75	80	22.86	24.384	1.524	19	Dry				
1162518	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	10:56	80	85	24.384	25.908	1.524	20	Dry				
1162519	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:01	85	90	25.908	27.432	1.524	20	Dry				
1162520	16QVV004	QVV	Corina Carlton CC02	Blank	2016-09-02	11:06			0	0	0						Coarse Blank
1162521	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:07	90	95	27.432	28.956	1.524	20	Dry				
1162522	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:12	95	100	28.956	30.48	1.524	20	Dry				
1162523	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:17	100	105	30.48	32.004	1.524	20	Dry				
1162524	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:21	105	110	32.004	33.528	1.524	19	Dry				
1162525	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:26	110	115	33.528	35.052	1.524	19	Dry				
1162526	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:33	115	120	35.052	36.576	1.524	19	Dry				
1162527	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:39	120	125	36.576	38.1	1.524	19	Dry				
1162528	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:45	125	130	38.1	39.624	1.524	20	Dry				
1162529	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	11:53	130	135	39.624	41.148	1.524	19	Dry				
1162530	16QVV004	QVV	Corina Carlton CC02	Duplicate	2016-09-02	12:01	130	135	39.624	41.148	1.524	19	Dry			1162529	
1162531	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:01	135	140	41.148	42.672	1.524	19	Dry				
1162532	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:05	140	145	42.672	44.196	1.524	19	Dry				
1162533	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:11	145	150	44.196	45.72	1.524	19	Dry				

1162534	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:15	150	155	45.72	47.244	1.524	19	Dry					
1162535	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:20	155	160	47.244	48.768	1.524	19	Dry					
1162536	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:25	160	165	48.768	50.292	1.524	20	Dry					
1162537	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:28	165	170	50.292	51.816	1.524	19	Dry					
1162538	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:35	170	175	51.816	53.34	1.524	19	Dry					
1162539	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:42	175	180	53.34	54.864	1.524	19	Dry					
1162540	16QVV004	QVV	Corina Carlton CC02	Standard	2016-09-02	12:50			0	0	0							CDN-ME-1205
1162541	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:50	180	185	54.864	56.388	1.524	19	Dry					
1162542	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	12:59	185	190	56.388	57.912	1.524	19	Dry					
1162543	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	13:05	190	195	57.912	59.436	1.524	19	Dry					
1162544	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	14:30	195	200	59.436	60.96	1.524	19	Dry					
1162545	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	14:37	200	205	60.96	62.484	1.524	20	Dry					
1162546	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	14:45	205	210	62.484	64.008	1.524	18	Dry					
1162547	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	14:53	210	215	64.008	65.532	1.524	19	Dry					
1162548	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:01	215	220	65.532	67.056	1.524	18	Dry					
1162549	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:11	220	225	67.056	68.58	1.524	19	Dry					
1162550	16QVV004	QVV	Corina Carlton CC02	Blank	2016-09-02	15:20			0	0	0							Coarse Blank
1162551	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:20	225	230	68.58	70.104	1.524	19	Dry					
1162552	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:26	230	235	70.104	71.628	1.524	18	Dry					
1162553	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:38	235	240	71.628	73.152	1.524	18	Dry					
1162554	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	15:50	240	245	73.152	74.676	1.524	18	Dry					
1162555	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:01	245	250	74.676	76.2	1.524	18	Dry					
1162556	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:08	250	255	76.2	77.724	1.524	18	Dry					
1162557	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:17	255	260	77.724	79.248	1.524	19	Dry					
1162558	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:25	260	265	79.248	80.772	1.524	19	Dry					
1162559	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:35	265	270	80.772	82.296	1.524	19	Dry					
1162560	16QVV004	QVV	Corina Carlton CC02	Duplicate	2016-09-02	16:45	265	270	80.772	82.296	1.524	19	Dry					1162559
1162561	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:45	270	275	82.296	83.82	1.524	19	Dry					
1162562	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	16:53	275	280	83.82	85.344	1.524	18	Dry					
1162563	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:01	280	285	85.344	86.868	1.524	18	Dry					
1162564	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:10	285	290	86.868	88.392	1.524	18	Dry					
1162565	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:20	290	295	88.392	89.916	1.524	18	Dry					
1162566	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:32	295	300	89.916	91.44	1.524	18	Dry					
1162567	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:42	300	305	91.44	92.964	1.524	18	Dry					
1162568	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:49	305	310	92.964	94.488	1.524	19	Dry					
1162569	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	17:57	310	315	94.488	96.012	1.524	16	Dry					
1162570	16QVV004	QVV	Corina Carlton CC02	Standard	2016-09-02	18:06			0	0	0							CDN-GS-1K
1162571	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-02	18:06	315	320	96.012	97.536	1.524	10	Dry					
1162572	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	07:46	320	325	97.536	99.06	1.524	25	Wet					
1162573	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	07:47	325	330	99.06	100.584	1.524	16	Wet					Fines washed away from water
1162574	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	08:31	330	335	100.584	102.108	1.524	16	Wet					Fines washed away from water
1162575	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	08:42	335	340	102.108	103.632	1.524	16	Wet					Fines washed away from water
1162576	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	08:58	340	345	103.632	105.156	1.524	12	Wet					Fines washed away from water
1162577	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	09:13	345	350	105.156	106.68	1.524	12	Wet					Fines washed away from water
1162578	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	09:33	350	355	106.68	108.204	1.524	12	Wet					Fines washed away from water
1162579	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	09:51	355	360	108.204	109.728	1.524	10	Wet					Fines washed away from water
1162580	16QVV004	QVV	Corina Carlton CC02	Blank	2016-09-03	10:05			0	0	0							Coarse Blank
1162581	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	10:05	360	365	109.728	111.252	1.524	10	Wet					Fines washed away from water
1162582	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	10:16	365	370	111.252	112.776	1.524	10	Wet					Fines washed away from water
1162583	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	10:31	370	375	112.776	114.3	1.524	10	Wet					Fines washed away from water
1162584	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	10:48	375	380	114.3	115.824	1.524	10	Wet					Fines washed away from water
1162585	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	11:05	380	385	115.824	117.348	1.524	10	Wet					Fines washed away from water
1162586	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	11:24	385	390	117.348	118.872	1.524	10	Wet					Fines washed away from water
1162587	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	11:43	390	395	118.872	120.396	1.524	8	Wet					Fines washed away from water
1162588	16QVV004	QVV	Corina Carlton CC02	Sample	2016-09-03	12:02	395	400	120.396	121.92	1.524	8	Wet					Fines washed away from water EOH
1162589	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	11:09	0	5	0	1.524	1.524	17	Dry					
1162590	16QVV005	QVV	Corina Carlton CC02	Duplicate	2016-09-04	11:19	0	5	0	1.524	1.524	17	Dry					1162589
1162591	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	11:19	5	10	1.524	3.048	1.524	20	Dry					
1162592	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	11:25	10	15	3.048	4.572	1.524	26	Dry					
1162593	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	11:36	15	20	4.572	6.096	1.524	28	Dry					
1162594	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	11:48	20	25	6.096	7.62	1.524	17	Dry					
1162595	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	12:18	25	30	7.62	9.144	1.524	18	Dry					
1162596	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	12:23	30	35	9.144	10.668	1.524	26	Dry					
1162597	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	15:40	35	40	10.668	12.192	1.524	26	Dry					

1162598	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	16:01		40	45	12.192	13.716	1.524		26	Dry				
1162599	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	16:39		45	50	13.716	15.24	1.524		30	Dry				
1162600	16QVV005	QVV	Corina Carlton CC02	Standard	2016-09-04	16:46				0	0	0							CDN-ME-1205
1162601	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	16:47		50	55	15.24	16.764	1.524		16	Dry				
1162602	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:01		55	60	16.764	18.288	1.524		19	Dry				
1162603	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:09		60	65	18.288	19.812	1.524		18	Dry				
1162604	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:13		65	70	19.812	21.336	1.524		18	Dry				
1162605	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:17		70	75	21.336	22.86	1.524		18	Dry				
1162606	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:21		75	80	22.86	24.384	1.524		18	Dry				
1162607	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:25		80	85	24.384	25.908	1.524		18	Dry				
1162608	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:27		85	90	25.908	27.432	1.524		20	Dry				
1162609	16QVV005	QVV	Corina Carlton CC02	Sample	2016-09-04	17:31		90	95	27.432	28.956	1.524		18	Dry				
1162610	16QVV006	QVV	Corina Carlton CC02	Standard	2016-09-06	08:07				0	0	0							CDN-GS-1K
1162611	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	08:08		0	5	0	1.524	1.524		16	Dry				
1162612	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	08:55		5	10	1.524	3.048	1.524		20	Dry				
1162613	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:05		10	15	3.048	4.572	1.524		22	Dry				
1162614	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:16		15	20	4.572	6.096	1.524		18	Dry				
1162615	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:40		20	25	6.096	7.62	1.524		19	Dry				
1162616	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:44		25	30	7.62	9.144	1.524		19	Dry				
1162617	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:47		30	35	9.144	10.668	1.524		20	Dry				
1162618	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:52		35	40	10.668	12.192	1.524		18	Dry				
1162619	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	09:56		40	45	12.192	13.716	1.524		18	Dry				
1162620	16QVV006	QVV	Corina Carlton CC02	Blank	2016-09-06	10:04				0	0	0							Coarse Blank
1162621	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:00		45	50	13.716	15.24	1.524		18	Dry				
1162622	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:04		50	55	15.24	16.764	1.524		18	Dry				
1162623	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:11		55	60	16.764	18.288	1.524		18	Dry				
1162624	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:15		60	65	18.288	19.812	1.524		18	Dry				
1162625	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:19		65	70	19.812	21.336	1.524		18	Dry				
1162626	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:24		70	75	21.336	22.86	1.524		16	Dry				
1162627	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:27		75	80	22.86	24.384	1.524		18	Dry				
1162628	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:31		80	85	24.384	25.908	1.524		20	Dry				
1162629	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:36		85	90	25.908	27.432	1.524		16	Dry				1162629
1162630	16QVV006	QVV	Corina Carlton CC02	Duplicate	2016-09-06	10:45		85	90	25.908	27.432	1.524		16	Dry				
1162631	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:46		90	95	27.432	28.956	1.524		18	Dry				
1162632	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:50		95	100	28.956	30.48	1.524		18	Dry				
1162633	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	10:57		100	105	30.48	32.004	1.524		18	Dry				
1162634	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:04		105	110	32.004	33.528	1.524		18	Dry				
1162635	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:10		110	115	33.528	35.052	1.524		18	Dry				
1162636	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:14		115	120	35.052	36.576	1.524		18	Dry				
1162637	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:21		120	125	36.576	38.1	1.524		19	Dry				
1162638	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:28		125	130	38.1	39.624	1.524		18	Dry				
1162639	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:36		130	135	39.624	41.148	1.524		18	Dry				
1162640	16QVV006	QVV	Corina Carlton CC02	Standard	2016-09-06	11:43				0	0	0							CDN-ME-1205
1162641	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:43		135	140	41.148	42.672	1.524		12	Dry				
1162642	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	11:50		140	145	42.672	44.196	1.524		18	Dry				
1162643	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:48		145	150	44.196	45.72	1.524		18	Dry				
1162644	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:49		150	155	45.72	47.244	1.524		16	Dry				
1162645	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:50		155	160	47.244	48.768	1.524		12	Dry				
1162646	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:50		160	165	48.768	50.292	1.524		18	Dry				
1162647	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:50		165	170	50.292	51.816	1.524		18	Dry				
1162648	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:50		170	175	51.816	53.34	1.524		16	Dry				
1162649	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:51		175	180	53.34	54.864	1.524		18	Dry				
1162650	16QVV006	QVV	Corina Carlton CC02	Blank	2016-09-06	18:51				0	0	0							Coarse Blank
1162651	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:52		180	185	54.864	56.388	1.524		20	Dry				
1162652	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:53		185	190	56.388	57.912	1.524		18	Dry				
1162653	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:53		190	195	57.912	59.436	1.524		18	Dry				
1162654	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:53		195	200	59.436	60.96	1.524		20	Dry				
1162655	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:53		200	205	60.96	62.484	1.524		20	Dry				
1162656	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:54		205	210	62.484	64.008	1.524		20	Dry				
1162657	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:54		210	215	64.008	65.532	1.524		18	Dry				
1162658	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:54		215	220	65.532	67.056	1.524		18	Dry				
1162659	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:54		220	225	67.056	68.58	1.524		16	Dry				
1162660	16QVV006	QVV	Corina Carlton CC02	Duplicate	2016-09-06	18:55		220	225	67.056	68.58	1.524		16	Dry				1162659
1162661	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:55		225	230	68.58	70.104	1.524		18	Dry				

1162662	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:55		230	235	70.104	71.628	1.524		20	Dry				
1162663	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:56		235	240	71.628	73.152	1.524		18	Dry				
1162664	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:56		240	245	73.152	74.676	1.524		20	Dry				
1162665	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:56		245	250	74.676	76.2	1.524		20	Dry				
1162666	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:56		250	255	76.2	77.724	1.524		20	Dry				
1162667	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:57		255	260	77.724	79.248	1.524		20	Dry				
1162668	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:57		260	265	79.248	80.772	1.524		20	Dry				
1162669	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:57		265	270	80.772	82.296	1.524		20	Dry				
1162670	16QVV006	QVV	Corina Carlton CC02	Standard	2016-09-06	18:58				0	0	0							CDN-GS-1K
1162671	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-06	18:58		270	275	82.296	83.82	1.524		16	Dry				
1162672	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	08:18		275	280	83.82	85.344	1.524		8	Wet	Small sample, water in hole			
1162673	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	08:41		280	285	85.344	86.868	1.524		18	Damp				
1162674	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	08:51		285	290	86.868	88.392	1.524		20	Dry				
1162675	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	09:02		290	295	88.392	89.916	1.524		20	Dry				
1162676	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	09:10		295	300	89.916	91.44	1.524		16	Dry				
1162677	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	09:22		300	305	91.44	92.964	1.524		16	Dry				
1162678	16QVV006	QVV	Corina Carlton CC02	Sample	2016-09-07	09:47		305	310	92.964	94.488	1.524		1	Dry	Small sample, loss of air EOH			
1162679	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	16:06		0	5	0	1.524	1.524		10	Dry				
1162680	16QVV007	QVV	Corina Carlton CC02	Blank	2016-09-07	16:21				0	0	0							Coarse Blank
1162681	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	16:21		5	10	1.524	3.048	1.524		18	Dry				
1162682	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	16:28		10	15	3.048	4.572	1.524		26	Dry				
1162683	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	16:37		15	20	4.572	6.096	1.524		18	Dry				
1162684	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:14		20	25	6.096	7.62	1.524		20	Dry				
1162685	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:18		25	30	7.62	9.144	1.524		20	Dry				
1162686	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:22		30	35	9.144	10.668	1.524		20	Dry				
1162687	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:27		35	40	10.668	12.192	1.524		20	Dry				
1162688	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:32		40	45	12.192	13.716	1.524		20	Dry				
1162689	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:37		45	50	13.716	15.24	1.524		20	Dry				
1162690	16QVV007	QVV	Corina Carlton CC02	Duplicate	2016-09-07	17:43		45	50	13.716	15.24	1.524		20	Dry			1162689	
1162691	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:43		50	55	15.24	16.764	1.524		20	Dry				
1162692	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:46		55	60	16.764	18.288	1.524		20	Dry				
1162693	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:50		60	65	18.288	19.812	1.524		20	Dry				
1162694	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:54		65	70	19.812	21.336	1.524		20	Dry				
1162695	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	17:58		70	75	21.336	22.86	1.524		20	Dry				
1162696	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:03		75	80	22.86	24.384	1.524		20	Dry				
1162697	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:09		80	85	24.384	25.908	1.524		20	Dry				
1162698	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:12		85	90	25.908	27.432	1.524		20	Dry				
1162699	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:17		90	95	27.432	28.956	1.524		20	Dry				
1162700	16QVV007	QVV	Corina Carlton CC02	Standard	2016-09-07	18:21				0	0	0							CDN-ME-1205
1162701	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:22		95	100	28.956	30.48	1.524		20	Dry				
1162702	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:26		100	105	30.48	32.004	1.524		21	Dry				
1162703	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:30		105	110	32.004	33.528	1.524		20	Dry				
1162704	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:36		110	115	33.528	35.052	1.524		20	Dry				
1162705	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:40		115	120	35.052	36.576	1.524		20	Dry				
1162706	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-07	18:45		120	125	36.576	38.1	1.524		20	Dry				
1162707	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	07:56		125	130	38.1	39.624	1.524		20	Dry				
1162708	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:25		130	135	39.624	41.148	1.524		20	Dry				
1162709	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:32		135	140	41.148	42.672	1.524		20	Dry				
1162710	16QVV007	QVV	Corina Carlton CC02	Standard	2016-09-08	08:36				0	0	0							CDN-GS-1K
1162711	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:36		140	145	42.672	44.196	1.524		20	Dry				
1162712	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:43		145	150	44.196	45.72	1.524		19	Dry				
1162713	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:50		150	155	45.72	47.244	1.524		18	Dry				
1162714	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	08:55		155	160	47.244	48.768	1.524		19	Dry				
1162715	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:01		160	165	48.768	50.292	1.524		19	Dry				
1162716	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:07		165	170	50.292	51.816	1.524		19	Dry				
1162717	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:15		170	175	51.816	53.34	1.524		19	Dry				
1162718	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:20		175	180	53.34	54.864	1.524		19	Dry				
1162719	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:26		180	185	54.864	56.388	1.524		20	Dry				
1162720	16QVV007	QVV	Corina Carlton CC02	Blank	2016-09-08	09:31				0	0	0							Coarse Blank
1162721	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:31		185	190	56.388	57.912	1.524		19	Dry				
1162722	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:36		190	195	57.912	59.436	1.524		20	Dry				
1162723	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:41		195	200	59.436	60.96	1.524		20	Dry				
1162724	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:47		200	205	60.96	62.484	1.524		20	Dry				
1162725	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:52		205	210	62.484	64.008	1.524		20	Dry				

1162726	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	09:58	210	215	64.008	65.532	1.524	19	Dry				
1162727	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:05	215	220	65.532	67.056	1.524	19	Dry				
1162728	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:11	220	225	67.056	68.58	1.524	20	Dry				
1162729	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:16	225	230	68.58	70.104	1.524	20	Dry				
1162730	16QVV007	QVV	Corina Carlton CC02	Duplicate	2016-09-08	10:23	225	230	68.58	70.104	1.524	20	Dry			1162729	
1162731	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:23	230	235	70.104	71.628	1.524	20	Dry				
1162732	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:27	235	240	71.628	73.152	1.524	20	Dry				
1162733	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:36	240	245	73.152	74.676	1.524	19	Dry				
1162734	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:44	245	250	74.676	76.2	1.524	20	Dry				
1162735	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:52	250	255	76.2	77.724	1.524	18	Dry				
1162736	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	10:58	255	260	77.724	79.248	1.524	20	Dry				
1162737	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:05	260	265	79.248	80.772	1.524	19	Dry				
1162738	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:22	265	270	80.772	82.296	1.524	19	Dry				
1162739	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:23	270	275	82.296	83.82	1.524	19	Dry				
1162740	16QVV007	QVV	Corina Carlton CC02	Standard	2016-09-08	11:31			0	0	0						CDN-ME-1205
1162741	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:31	275	280	83.82	85.344	1.524	19	Dry				
1162742	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:37	280	285	85.344	86.868	1.524	20	Dry				
1162743	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:44	285	290	86.868	88.392	1.524	20	Dry				
1162744	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:49	290	295	88.392	89.916	1.524	20	Dry				
1162745	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	11:56	295	300	89.916	91.44	1.524	19	Dry				
1162746	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:06	300	305	91.44	92.964	1.524	19	Dry				
1162747	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:11	305	310	92.964	94.488	1.524	19	Dry				
1162748	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:20	310	315	94.488	96.012	1.524	19	Dry				
1162749	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:29	315	320	96.012	97.536	1.524	19	Dry				
1162750	16QVV007	QVV	Corina Carlton CC02	Blank	2016-09-08	12:38			0	0	0						Coarse Blank
1162751	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:39	320	325	97.536	99.06	1.524	19	Dry				
1162752	16QVV007	QVV	Corina Carlton CC02	Sample	2016-09-08	12:49	325	330	99.06	100.584	1.524	19	Dry			EOH	
1162753	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	08:36	0	5	0	1.524	1.524	16	Dry				
1162754	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	08:51	5	10	1.524	3.048	1.524	18	Dry				
1162755	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	09:01	10	15	3.048	4.572	1.524	18	Dry				
1162756	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	09:12	15	20	4.572	6.096	1.524	26	Dry				
1162757	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	09:21	20	25	6.096	7.62	1.524	24	Dry				
1162758	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	09:34	25	30	7.62	9.144	1.524	18	Dry			Open hole	
1162759	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:04	30	35	9.144	10.668	1.524	19	Dry				
1162760	16QVV008	QVV	Corina Carlton CC02	Duplicate	2016-09-09	10:12	30	35	9.144	10.668	1.524	19	Dry			1162759	
1162761	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:12	35	40	10.668	12.192	1.524	19	Dry				
1162762	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:15	40	45	12.192	13.716	1.524	18	Dry				
1162763	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:15	45	50	13.716	15.24	1.524	19	Dry				
1162764	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:18	50	55	15.24	16.764	1.524	20	Dry				
1162765	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:21	55	60	16.764	18.288	1.524	20	Dry				
1162766	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:24	60	65	18.288	19.812	1.524	20	Dry				
1162767	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:30	65	70	19.812	21.336	1.524	19	Dry				
1162768	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:34	70	75	21.336	22.86	1.524	20	Dry				
1162769	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:39	75	80	22.86	24.384	1.524	20	Dry				
1162770	16QVV008	QVV	Corina Carlton CC02	Standard	2016-09-09	10:24			0	0	0						CDN-GS-1K
1162771	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:44	80	85	24.384	25.908	1.524	20	Dry				
1162772	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:49	85	90	25.908	27.432	1.524	20	Dry				
1162773	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:55	90	95	27.432	28.956	1.524	20	Dry				
1162774	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	10:58	95	100	28.956	30.48	1.524	18	Dry				
1162775	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:03	100	105	30.48	32.004	1.524	20	Dry				
1162776	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:10	105	110	32.004	33.528	1.524	19	Dry				
1162777	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:17	110	115	33.528	35.052	1.524	19	Dry				
1162778	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:22	115	120	35.052	36.576	1.524	20	Dry				
1162779	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:27	120	125	36.576	38.1	1.524	20	Dry				
1162780	16QVV008	QVV	Corina Carlton CC02	Blank	2016-09-09	11:34			0	0	0						Coarse Blank
1162781	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:34	125	130	38.1	39.624	1.524	19	Dry				
1162782	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:41	130	135	39.624	41.148	1.524	19	Dry				
1162783	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	11:47	135	140	41.148	42.672	1.524	19	Dry				
1162784	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:04	140	145	42.672	44.196	1.524	19	Dry				
1162785	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:10	145	150	44.196	45.72	1.524	19	Dry				
1162786	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:16	150	155	45.72	47.244	1.524	20	Dry				
1162787	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:20	155	160	47.244	48.768	1.524	20	Dry				
1162788	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:26	160	165	48.768	50.292	1.524	19	Dry				
1162789	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:31	165	170	50.292	51.816	1.524	19	Dry				

1162790	16QVV008	QVV	Corina Carlton CC02	Duplicate	2016-09-09	12:39	165	170	50.292	51.816	1.524	19	Dry		1162789	
1162791	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:39	170	175	51.816	53.34	1.524	19	Dry			
1162792	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:44	175	180	53.34	54.864	1.524	19	Dry			
1162793	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:51	180	185	54.864	56.388	1.524	20	Dry			
1162794	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	12:58	185	190	56.388	57.912	1.524	19	Dry			
1162795	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	13:03	190	195	57.912	59.436	1.524	19	Dry			
1162796	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	13:09	195	200	59.436	60.96	1.524	19	Dry			
1162797	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	13:17	200	205	60.96	62.484	1.524	19	Dry			
1162798	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:03	205	210	62.484	64.008	1.524	19	Dry			
1162799	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:13	210	215	64.008	65.532	1.524	19	Dry			
1162800	16QVV008	QVV	Corina Carlton CC02	Standard	2016-09-09	16:19			0	0	0					CDN-ME-1205
1162801	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:19	215	220	65.532	67.056	1.524	19	Dry			
1162802	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:27	220	225	67.056	68.58	1.524	19	Dry			
1162803	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:33	225	230	68.58	70.104	1.524	19	Dry			
1162804	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:40	230	235	70.104	71.628	1.524	19	Dry			
1162805	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:48	235	240	71.628	73.152	1.524	19	Dry			
1162806	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:55	240	245	73.152	74.676	1.524	19	Dry			
1162807	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:03	245	250	74.676	76.2	1.524	19	Dry			
1162808	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:10	250	255	76.2	77.724	1.524	19	Dry			
1162809	16QVV008	QVV	Corina Carlton CC03	Sample	2016-09-09	17:17	255	260	77.724	79.248	1.524	19	Dry			
1162810	16QVV008	QVV	Corina Carlton CC04	Standard	2016-09-09	17:24										
1162811	16QVV008	QVV	Corina Carlton CC05	Sample	2016-09-09	17:31	260	265	79.248	80.772	1.524	19	Dry			
1162812	16QVV008	QVV	Corina Carlton CC06	Sample	2016-09-09	17:38	265	270	80.772	82.296	1.524	19	Dry			
1162813	16QVV008	QVV	Corina Carlton CC07	Sample	2016-09-09	17:45	270	275	82.296	83.82	1.524	19	Dry			
1162814	16QVV008	QVV	Corina Carlton CC08	Sample	2016-09-09	17:52	275	280	83.82	85.344	1.524	19	Dry			
1162815	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	15:56	280	285	85.344	86.868	1.524	19	Dry			
1162816	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:05	285	290	86.868	88.392	1.524	8	Dry			
1162817	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:15	290	295	88.392	89.916	1.524	8	Dry			
1162818	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:27	295	300	89.916	91.44	1.524	8	Dry			
1162819	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:44	300	305	91.44	92.964	1.524	6	Dry			
1162820	16QVV008	QVV	Corina Carlton CC02	Blank	2016-09-09	16:57			0	0	0					Coarse Blank
1162821	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	16:58	305	310	92.964	94.488	1.524	10	Dry			
1162822	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:14	310	315	94.488	96.012	1.524	12	Dry			
1162823	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:27	315	320	96.012	97.536	1.524	16	Dry			
1162824	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:37	320	325	97.536	99.06	1.524	18	Dry			
1162825	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:46	325	330	99.06	100.584	1.524	20	Dry			
1162826	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	17:55	330	335	100.584	102.108	1.524	20	Dry			
1162827	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	18:02	335	340	102.108	103.632	1.524	21	Dry			
1162828	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	18:09	340	345	103.632	105.156	1.524	21	Dry			
1162829	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-09	18:17	345	350	105.156	106.68	1.524	21	Dry			
1162830	16QVV008	QVV	Corina Carlton CC02	Duplicate	2016-09-09	18:35	345	350	105.156	106.68	1.524	21	Dry			1162829
1162831	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	09:07	350	355	106.68	108.204	1.524	16	Wet			
1162832	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	09:41	355	360	108.204	109.728	1.524	6	Wet			Small sample
1162833	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	09:53	360	365	109.728	111.252	1.524	16	Wet			
1162834	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:10	365	370	111.252	112.776	1.524	16	Wet			
1162835	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:18	370	375	112.776	114.3	1.524	16	Wet			
1162836	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:24	375	380	114.3	115.824	1.524	22	Damp			
1162837	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:32	380	385	115.824	117.348	1.524	20	Damp			
1162838	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:38	385	390	117.348	118.872	1.524	20	Damp			
1162839	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:46	390	395	118.872	120.396	1.524	26	Damp			
1162840	16QVV008	QVV	Corina Carlton CC02	Standard	2016-09-10	10:56			0	0	0					CDN-ME-1205
1162841	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	10:56	395	400	120.396	121.92	1.524	24	Damp			
1162842	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:07	400	405	121.92	123.444	1.524	24	Damp			
1162843	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:11	405	410	123.444	124.968	1.524	16	Damp			
1162844	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:24	410	415	124.968	126.492	1.524	20	Damp			
1162845	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:28	415	420	126.492	128.016	1.524	24	Damp			
1162846	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:38	420	425	128.016	129.54	1.524	24	Damp			
1162847	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	11:51	425	430	129.54	131.064	1.524	20	Damp			
1162848	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:01	430	435	131.064	132.588	1.524	24	Damp			
1162849	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:12	435	440	132.588	134.112	1.524	20	Damp			
1162850	16QVV008	QVV	Corina Carlton CC02	Blank	2016-09-10	12:23			0	0	0					Coarse Blank
1162851	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:24	440	445	134.112	135.636	1.524	22	Damp			
1162852	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:33	445	450	135.636	137.16	1.524	24	Damp			
1162853	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:46	450	455	137.16	138.684	1.524	26	Damp			

1162854	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	12:58	455	460	138.684	140.208	1.524	24	Damp				
1162855	16QVV008	QVV	Corina Carlton CC02	Sample	2016-09-10	13:09	460	465	140.208	141.732	1.524	24	Damp	EOH			
1162856	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	09:13	0	5	0	1.524	1.524	20	Dry				
1162857	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	09:54	5	10	1.524	3.048	1.524	18	Dry				
1162858	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:02	10	15	3.048	4.572	1.524	19	Dry				
1162859	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:10	15	20	4.572	6.096	1.524	30	Dry				
1162860	16QVV009	QVV	Corina Carlton CC02	Duplicate	2016-09-11	10:23	15	20	4.572	6.096	1.524	30	Dry		1162859		
1162861	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:24	20	25	6.096	7.62	1.524	19	Dry	Open hole			
1162862	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:33	25	30	7.62	9.144	1.524	20	Dry				
1162863	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:36	30	35	9.144	10.668	1.524	18	Dry				
1162864	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:38	35	40	10.668	12.192	1.524	19	Dry				
1162865	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:41	40	45	12.192	13.716	1.524	18	Dry				
1162866	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:43	45	50	13.716	15.24	1.524	18	Dry				
1162867	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:48	50	55	15.24	16.764	1.524	16	Dry				
1162868	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:49	55	60	16.764	18.288	1.524	19	Dry				
1162869	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:52	60	65	18.288	19.812	1.524	19	Dry				
1162870	16QVV009	QVV	Corina Carlton CC02	Standard	2016-09-11	10:55			0	0	0						CDN-GS-1K
1162871	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:55	65	70	19.812	21.336	1.524	20	Dry				
1162872	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	10:57	70	75	21.336	22.86	1.524	20	Dry				
1162873	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:00	75	80	22.86	24.384	1.524	21	Dry				
1162874	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:03	80	85	24.384	25.908	1.524	20	Dry				
1162875	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:07	85	90	25.908	27.432	1.524	20	Dry				
1162876	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:10	90	95	27.432	28.956	1.524	20	Dry				
1162877	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:13	95	100	28.956	30.48	1.524	20	Dry				
1162878	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:17	100	105	30.48	32.004	1.524	20	Dry				
1162879	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:20	105	110	32.004	33.528	1.524	20	Dry				
1162880	16QVV009	QVV	Corina Carlton CC02	Blank	2016-09-11	11:26			0	0	0						Coarse Blank
1162881	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:26	110	115	33.528	35.052	1.524	20	Dry				
1162882	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:30	115	120	35.052	36.576	1.524	20	Dry				
1162883	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:38	120	125	36.576	38.1	1.524	20	Dry				
1162884	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:44	125	130	38.1	39.624	1.524	20	Dry				
1162885	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:50	130	135	39.624	41.148	1.524	20	Dry				
1162886	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	11:55	135	140	41.148	42.672	1.524	19	Dry				
1162887	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:01	140	145	42.672	44.196	1.524	20	Dry				
1162888	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:08	145	150	44.196	45.72	1.524	20	Dry				
1162889	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:13	150	155	45.72	47.244	1.524	18	Dry				
1162890	16QVV009	QVV	Corina Carlton CC02	Duplicate	2016-09-11	12:18	150	155	45.72	47.244	1.524	18	Dry		1162889		
1162891	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:18	155	160	47.244	48.768	1.524	19	Dry				
1162892	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:23	160	165	48.768	50.292	1.524	19	Dry				
1162893	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:29	165	170	50.292	51.816	1.524	19	Dry				
1162894	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:36	170	175	51.816	53.34	1.524	19	Dry				
1162895	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:41	175	180	53.34	54.864	1.524	19	Dry				
1162896	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:48	180	185	54.864	56.388	1.524	19	Dry				
1162897	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	12:54	185	190	56.388	57.912	1.524	19	Dry				
1162898	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	13:00	190	195	57.912	59.436	1.524	19	Dry				
1162899	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	13:53	195	200	59.436	60.96	1.524	19	Dry				
1162900	16QVV009	QVV	Corina Carlton CC02	Standard	2016-09-11	14:05			0	0	0						CDN-ME-1205
1162901	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:06	200	205	60.96	62.484	1.524	19	Dry				
1162902	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:13	205	210	62.484	64.008	1.524	19	Dry				
1162903	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:20	210	215	64.008	65.532	1.524	19	Dry				
1162904	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:29	215	220	65.532	67.056	1.524	19	Dry				
1162905	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:36	220	225	67.056	68.58	1.524	19	Dry				
1162906	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:43	225	230	68.58	70.104	1.524	19	Dry				
1162907	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:50	230	235	70.104	71.628	1.524	19	Dry				
1162908	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	14:57	235	240	71.628	73.152	1.524	19	Dry				
1162909	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:03	240	245	73.152	74.676	1.524	19	Dry				
1162910	16QVV009	QVV	Corina Carlton CC02	Standard	2016-09-11	15:11			0	0	0						CDN-GS-1K
1162911	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:11	245	250	74.676	76.2	1.524	19	Dry				
1162912	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:20	250	255	76.2	77.724	1.524	19	Dry				
1162913	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:28	255	260	77.724	79.248	1.524	19	Dry				
1162914	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:36	260	265	79.248	80.772	1.524	19	Dry				
1162915	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:44	265	270	80.772	82.296	1.524	19	Dry				
1162916	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	15:52	270	275	82.296	83.82	1.524	19	Dry				
1162917	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:00	275	280	83.82	85.344	1.524	20	Dry				

1162918	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:08	280	285	85.344	86.868	1.524	20	Dry				
1162919	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:16	285	290	86.868	88.392	1.524	20	Dry				
1162920	16QVV009	QVV	Corina Carlton CC02	Blank	2016-09-11	16:25			0	0	0						Coarse Blank
1162921	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:25	290	295	88.392	89.916	1.524	20	Dry				
1162922	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:33	295	300	89.916	91.44	1.524	20	Dry				
1162923	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:44	300	305	91.44	92.964	1.524	20	Dry				
1162924	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:50	305	310	92.964	94.488	1.524	20	Dry				
1162925	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	16:59	310	315	94.488	96.012	1.524	20	Dry				
1162926	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:08	315	320	96.012	97.536	1.524	20	Dry				
1162927	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:16	320	325	97.536	99.06	1.524	19	Dry				
1162928	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:25	325	330	99.06	100.584	1.524	19	Dry				
1162929	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:33	330	335	100.584	102.108	1.524	19	Dry				
1162930	16QVV009	QVV	Corina Carlton CC02	Duplicate	2016-09-11	17:43	330	335	100.584	102.108	1.524	19	Dry			1162929	
1162931	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:43	335	340	102.108	103.632	1.524	21	Dry				
1162932	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	17:51	340	345	103.632	105.156	1.524	21	Dry				
1162933	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	18:01	345	350	105.156	106.68	1.524	21	Dry				
1162934	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-11	18:11	350	355	106.68	108.204	1.524	21	Dry				
1162935	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	08:03	355	360	108.204	109.728	1.524	5	Wet				Fines washed away from water High potential for contamination - washing sides of hole
1162936	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	09:20	360	365	109.728	111.252	1.524	5	Wet				Lack of fines due to wet hole
1162937	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	09:47	365	370	111.252	112.776	1.524	18	Damp				
1162938	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	10:04	375	375	112.776	114.3	1.524	22	Damp				
1162939	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	10:21	375	380	114.3	115.824	1.524	24	Damp				
1162940	16QVV009	QVV	Corina Carlton CC02	Standard	2016-09-12	10:34			0	0	0						CDN-ME-1205
1162941	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	10:34	380	385	115.824	117.348	1.524	24	Damp				
1162942	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	10:51	385	390	117.348	118.872	1.524	16	Damp				
1162943	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	11:03	390	395	118.872	120.396	1.524	18	Damp				
1162944	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	11:19	395	400	120.396	121.92	1.524	16	Damp				
1162945	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	11:34	400	405	121.92	123.444	1.524	22	Damp				
1162946	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	11:59	405	410	123.444	124.968	1.524	20	Damp				
1162947	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	12:07	410	415	124.968	126.492	1.524	22	Damp				
1162948	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	12:27	415	420	126.492	128.016	1.524	18	Damp				
1162949	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	12:40	420	425	128.016	129.54	1.524	20	Damp				
1162950	16QVV009	QVV	Corina Carlton CC02	Blank	2016-09-12	13:06			0	0	0						Coarse Blank
1162951	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	13:07	425	430	129.54	131.064	1.524	18	Damp				
1162952	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	14:12	430	435	131.064	132.588	1.524	8	Damp				
1162953	16QVV009	QVV	Corina Carlton CC02	Sample	2016-09-12	14:45	435	440	132.588	134.112	1.524	4	Damp				Drilled half of rod. Hole was called. EOH
1184501	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	10:57	0	5	0	1.524	1.524	14	Dry				
1184502	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:15	5	10	1.524	3.048	1.524	19	Dry				
1184503	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:20	10	15	3.048	4.572	1.524	28	Dry				
1184504	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:30	15	20	4.572	6.096	1.524	18	Dry				Open hole
1184505	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:45	20	25	6.096	7.62	1.524	18	Dry				
1184506	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:49	25	30	7.62	9.144	1.524	18	Dry				
1184507	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:53	30	35	9.144	10.668	1.524	18	Dry				
1184508	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	11:56	35	40	10.668	12.192	1.524	18	Dry				
1184509	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:01	40	45	12.192	13.716	1.524	18	Dry				
1184510	16QVV010	QVV	Corina Carlton CC02	Standard	2016-09-13	12:04			0	0	0						CDN-GS-1K
1184511	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:05	45	50	13.716	15.24	1.524	12	Dry				
1184512	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:08	50	55	15.24	16.764	1.524	20	Dry				
1184513	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:12	55	60	16.764	18.288	1.524	18	Dry				
1184514	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:15	60	65	18.288	19.812	1.524	20	Dry				
1184515	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:19	65	70	19.812	21.336	1.524	20	Dry				
1184516	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:23	70	75	21.336	22.86	1.524	20	Dry				
1184517	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:27	75	80	22.86	24.384	1.524	20	Dry				
1184518	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	12:34	80	85	24.384	25.908	1.524	20	Dry				
1184519	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:12	85	90	25.908	27.432	1.524	20	Dry				
1184520	16QVV010	QVV	Corina Carlton CC02	Blank	2016-09-13	13:17			0	0	0						Coarse Blank
1184521	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:18	90	95	27.432	28.956	1.524	19	Dry				
1184522	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:24	95	100	28.956	30.48	1.524	20	Dry				
1184523	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:31	100	105	30.48	32.004	1.524	19	Dry				
1184524	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:36	105	110	32.004	33.528	1.524	20	Dry				
1184525	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:42	110	115	33.528	35.052	1.524	19	Dry				
1184526	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:47	115	120	35.052	36.576	1.524	19	Dry				
1184527	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:52	120	125	36.576	38.1	1.524	20	Dry				

1184528	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:55	125	130	38.1	39.624	1.524	20	Dry					
1184529	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	13:59	130	135	39.624	41.148	1.524	16	Dry					
1184530	16QVV010	QVV	Corina Carlton CC02	Duplicate	2016-09-13	14:16	130	135	39.624	41.148	1.524	16	Dry				1184529	
1184531	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	14:16	135	140	41.148	42.672	1.524	19	Dry					
1184532	16QVV010	QVV	Corina Carlton CC02	Sample	2016-09-13	14:29	140	145	42.672	44.196	1.524	19	Dry	EOH				
1184533	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	09:55	0	5	0	1.524	1.524	18	Dry					
1184534	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	10:11	5	10	1.524	3.048	1.524	8	Dry					
1184535	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	10:18	10	15	3.048	4.572	1.524	20	Dry					
1184536	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	10:28	15	20	4.572	6.096	1.524	20	Dry					
1184537	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	10:37	20	25	6.096	7.62	1.524	18	Dry	Open hole				
1184538	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	11:54	25	30	7.62	9.144	1.524	18	Dry					
1184539	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	11:59	30	35	9.144	10.668	1.524	18	Dry					
1184540	16QVV011	QVV	Corina Carlton CC02	Standard	2016-09-15	12:03			0	0	0						CDN-ME-1205	
1184541	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:03	35	40	10.668	12.192	1.524	19	Dry					
1184542	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:08	40	45	12.192	13.716	1.524	19	Dry					
1184543	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:15	45	50	13.716	15.24	1.524	19	Dry					
1184544	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:21	50	55	15.24	16.764	1.524	19	Dry					
1184545	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:28	55	60	16.764	18.288	1.524	19	Dry					
1184546	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	12:34	60	65	18.288	19.812	1.524	19	Dry					
1184547	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	13:48	65	70	19.812	21.336	1.524	19	Dry					
1184548	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	13:54	70	75	21.336	22.86	1.524	19	Dry					
1184549	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:01	75	80	22.86	24.384	1.524	19	Dry					
1184550	16QVV011	QVV	Corina Carlton CC02	Blank	2016-09-15	14:06			0	0	0						Coarse Blank	
1184551	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:07	80	85	24.384	25.908	1.524	19	Dry					
1184552	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:10	85	90	25.908	27.432	1.524	19	Dry					
1184553	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:17	90	95	27.432	28.956	1.524	18	Dry					
1184554	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:25	95	100	28.956	30.48	1.524	18	Dry					
1184555	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:32	100	105	30.48	32.004	1.524	18	Dry					
1184556	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:39	105	110	32.004	33.528	1.524	18	Dry					
1184557	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:47	110	115	33.528	35.052	1.524	18	Dry					
1184558	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	14:54	115	120	35.052	36.576	1.524	16	Dry					
1184559	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:00	120	125	36.576	38.1	1.524	20	Dry					
1184560	16QVV011	QVV	Corina Carlton CC02	Duplicate	2016-09-15	15:15	120	125	36.576	38.1	1.524	20	Dry				1184559	
1184561	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:16	125	130	38.1	39.624	1.524	19	Dry					
1184562	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:22	130	135	39.624	41.148	1.524	19	Dry					
1184563	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:31	135	140	41.148	42.672	1.524	19	Dry					
1184564	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:40	140	145	42.672	44.196	1.524	19	Dry					
1184565	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	15:50	145	150	44.196	45.72	1.524	19	Dry					
1184566	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:00	150	155	45.72	47.244	1.524	19	Dry					
1184567	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:11	155	160	47.244	48.768	1.524	19	Dry					
1184568	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:21	160	165	48.768	50.292	1.524	19	Dry					
1184569	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:33	165	170	50.292	51.816	1.524	19	Dry					
1184570	16QVV011	QVV	Corina Carlton CC02	Standard	2016-09-15	16:41			0	0	0						CDN-GS-1K	
1184571	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:42	170	175	51.816	53.34	1.524	19	Dry					
1184572	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:50	175	180	53.34	54.864	1.524	19	Dry					
1184573	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	16:59	180	185	54.864	56.388	1.524	19	Dry					
1184574	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:08	185	190	56.388	57.912	1.524	19	Dry					
1184575	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:16	190	195	57.912	59.436	1.524	19	Dry					
1184576	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:25	195	200	59.436	60.96	1.524	19	Dry					
1184577	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:32	200	205	60.96	62.484	1.524	19	Dry					
1184578	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:39	205	210	62.484	64.008	1.524	19	Dry					
1184579	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:48	210	215	64.008	65.532	1.524	18	Dry					
1184580	16QVV011	QVV	Corina Carlton CC02	Blank	2016-09-15	17:58			0	0	0						Coarse Blank	
1184581	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	17:58	215	220	65.532	67.056	1.524	19	Dry					
1184582	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	18:06	220	225	67.056	68.58	1.524	19	Dry					
1184583	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	18:15	225	230	68.58	70.104	1.524	19	Dry					
1184584	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-15	18:23	230	235	70.104	71.628	1.524	19	Dry					
1184585	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	09:38	235	240	71.628	73.152	1.524	20	Dry					
1184586	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	09:54	240	245	73.152	74.676	1.524	19	Dry					
1184587	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:04	245	250	74.676	76.2	1.524	19	Dry					
1184588	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:15	250	255	76.2	77.724	1.524	19	Dry					
1184589	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:47	255	260	77.724	79.248	1.524	20	Dry					
1184590	16QVV011	QVV	Corina Carlton CC02	Duplicate	2016-09-16	10:47	255	260	77.724	79.248	1.524	20	Dry				1184589	
1184591	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:47	260	265	79.248	80.772	1.524	16	Dry					

1184592	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:48	265	270	80.772	82.296	1.524	20	Dry					
1184593	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	10:58	270	275	82.296	83.82	1.524	20	Dry					
1184594	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	11:05	275	280	83.82	85.344	1.524	20	Dry					
1184595	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	11:15	280	285	85.344	86.868	1.524	18	Dry					
1184596	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	11:30	285	290	86.868	88.392	1.524	19	Dry					
1184597	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	11:40	290	295	88.392	89.916	1.524	18	Dry					
1184598	16QVV011	QVV	Corina Carlton CC02	Sample	2016-09-16	11:54	295	300	89.916	91.44	1.524	19	Dry	EOH				
1184599	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	14:39	0	5	0	1.524	1.524	12	Dry					
1184600	16QVV012	QVV	Corina Carlton CC02	Standard	2016-09-16	15:29			0	0	0							CDN-ME-1205
1184601	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	15:29	5	10	1.524	3.048	1.524	12	Dry					
1184602	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	15:36	10	15	3.048	4.572	1.524	20	Dry					
1184603	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	15:46	15	20	4.572	6.096	1.524	16	Dry	Open hole				
1184604	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:08	20	25	6.096	7.62	1.524	19	Dry					
1184605	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:12	25	30	7.62	9.144	1.524	19	Dry					
1184606	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:18	30	35	9.144	10.668	1.524	19	Dry					
1184607	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:25	35	40	10.668	12.192	1.524	19	Dry					
1184608	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:29	40	45	12.192	13.716	1.524	19	Dry					
1184609	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:32	45	50	13.716	15.24	1.524	19	Dry					
1184610	16QVV012	QVV	Corina Carlton CC02	Standard	2016-09-16	16:36			0	0	0							CDN-GS-1K
1184611	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:36	50	55	15.24	16.764	1.524	19	Dry					
1184612	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:40	55	60	16.764	18.288	1.524	19	Dry					
1184613	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:45	60	65	18.288	19.812	1.524	19	Dry					
1184614	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:49	65	70	19.812	21.336	1.524	19	Dry					
1184615	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:54	70	75	21.336	22.86	1.524	19	Dry					
1184616	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	16:59	75	80	22.86	24.384	1.524	19	Dry					
1184617	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	17:04	80	85	24.384	25.908	1.524	19	Dry					
1184618	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	17:21	85	90	25.908	27.432	1.524	19	Dry					
1184619	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	17:27	90	95	27.432	28.956	1.524	19	Dry					
1184620	16QVV012	QVV	Corina Carlton CC03	Blank	2016-09-16	17:33												
1184621	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	17:35	95	100	28.956	30.48	1.524	19	Dry					
1184622	16QVV012	QVV	Corina Carlton CC02	Sample	2016-09-16	17:43	100	105	30.48	32.004	1.524	16	Dry	EOH				
1184623	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-17	19:16	0	5	0	1.524	1.524	0.5	Wet					
1184624	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-17	19:57	5	10	1.524	3.048	1.524	22	Wet					
1184625	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-17	20:25	10	15	3.048	4.572	1.524	20	Wet					
1184626	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	09:11	15	20	4.572	6.096	1.524	22	Wet	Frozen				
1184627	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	10:12	20	25	6.096	7.62	1.524	36	Damp					
1184628	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	10:29	25	30	7.62	9.144	1.524	38	Damp					
1184629	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	10:59	30	35	9.144	10.668	1.524	18	Dry	Open hole				
1184630	16QVV013	QVV	Corina Carlton CC02	Duplicate	2016-09-18	11:06	30	35	9.144	10.668	1.524	18	Dry	Open hole	1184629			
1184631	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:06	35	40	10.668	12.192	1.524	20	Dry					
1184632	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:11	40	45	12.192	13.716	1.524	20	Dry					
1184633	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:17	45	50	13.716	15.24	1.524	20	Dry					
1184634	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:25	50	55	15.24	16.764	1.524	20	Dry					
1184635	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:31	55	60	16.764	18.288	1.524	20	Dry					
1184636	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:36	60	65	18.288	19.812	1.524	20	Dry					
1184637	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:42	65	70	19.812	21.336	1.524	20	Dry					
1184638	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:48	70	75	21.336	22.86	1.524	20	Dry					
1184639	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	11:53	75	80	22.86	24.384	1.524	20	Dry					
1184640	16QVV013	QVV	Corina Carlton CC02	Standard	2016-09-18	12:03			0	0	0							CDN-ME-1205
1184641	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	12:03	80	85	24.384	25.908	1.524	20	Dry					
1184642	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	12:11	85	90	25.908	27.432	1.524	20	Dry					
1184643	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	12:16	90	95	27.432	28.956	1.524	20	Dry					
1184644	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	12:21	95	100	28.956	30.48	1.524	20	Dry					
1184645	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:13	100	105	30.48	32.004	1.524	20	Dry					
1184646	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:17	105	110	32.004	33.528	1.524	20	Dry					
1184647	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:24	110	115	33.528	35.052	1.524	20	Dry					
1184648	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:28	115	120	35.052	36.576	1.524	20	Dry					
1184649	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:34	120	125	36.576	38.1	1.524	20	Dry					
1184650	16QVV013	QVV	Corina Carlton CC02	Blank	2016-09-18	13:42			0	0	0							Coarse Blank
1184651	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:42	125	130	38.1	39.624	1.524	20	Dry					
1184652	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	13:52	130	135	39.624	41.148	1.524	19	Dry					
1184653	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:02	135	140	41.148	42.672	1.524	20	Dry					
1184654	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:13	140	145	42.672	44.196	1.524	20	Dry					
1184655	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:25	145	150	44.196	45.72	1.524	18	Dry					

1184656	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:34	150	155	45.72	47.244	1.524	18	Dry					
1184657	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:43	155	160	47.244	48.768	1.524	18	Dry					
1184658	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:52	160	165	48.768	50.292	1.524	18	Dry					
1184659	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	14:58	165	170	50.292	51.816	1.524	18	Dry					
1184660	16QVV013	QVV	Corina Carlton CC02	Duplicate	2016-09-18	15:08	165	170	50.292	51.816	1.524	18	Dry			1184659		
1184661	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	15:09	170	175	51.816	53.34	1.524	18	Dry					
1184662	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	15:18	175	180	53.34	54.864	1.524	18	Dry					
1184663	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	15:36	180	185	54.864	56.388	1.524	18	Dry					
1184664	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	15:44	185	190	56.388	57.912	1.524	20	Dry					
1184665	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	15:59	190	195	57.912	59.436	1.524	19	Dry					
1184666	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	16:12	195	200	59.436	60.96	1.524	20	Dry					
1184667	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	16:26	200	205	60.96	62.484	1.524	5	Dry					
1184668	16QVV013	QVV	Corina Carlton CC02	Sample	2016-09-18	17:23	205	210	62.484	64.008	1.524	4	Wet	EOH				
1184669	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	15:53	0	5	0	1.524	1.524	10	Damp					
1184670	16QVV014	QVV	Corina Carlton CC02	Standard	2016-09-19	16:01			0	0	0							CDN-GS-1K
1184671	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	16:02	5	10	1.524	3.048	1.524	20	Damp					
1184672	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	16:27	10	15	3.048	4.572	1.524	20	Damp					
1184673	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	16:31	15	20	4.572	6.096	1.524	22	Damp					
1184674	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	16:44	20	25	6.096	7.62	1.524	30	Damp					
1184675	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:02	25	30	7.62	9.144	1.524	32	Damp					
1184676	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:15	30	35	9.144	10.668	1.524	18	Dry	Open hole				
1184677	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:39	35	40	10.668	12.192	1.524	19	Dry					
1184678	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:44	40	45	12.192	13.716	1.524	19	Dry					
1184679	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:49	45	50	13.716	15.24	1.524	19	Dry					
1184680	16QVV014	QVV	Corina Carlton CC02	Blank	2016-09-19	17:53			0	0	0							
1184681	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:53	50	55	15.24	16.764	1.524	19	Dry					
1184682	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	17:55	55	60	16.764	18.288	1.524	19	Dry					
1184683	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:00	60	65	18.288	19.812	1.524	19	Dry					
1184684	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:05	65	70	19.812	21.336	1.524	19	Dry					
1184685	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:11	70	75	21.336	22.86	1.524	19	Dry					
1184686	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:16	75	80	22.86	24.384	1.524	19	Dry					
1184687	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:24	80	85	24.384	25.908	1.524	19	Dry					
1184688	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:30	85	90	25.908	27.432	1.524	19	Dry					
1184689	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:38	90	95	27.432	28.956	1.524	19	Dry					
1184690	16QVV014	QVV	Corina Carlton CC02	Duplicate	2016-09-20	16:11	90	95	27.432	28.956	1.524	19	Dry			1184689		
1184691	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:50	95	100	28.956	30.48	1.524	19	Dry					
1184692	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:50	100	105	30.48	32.004	1.524	19	Dry					
1184693	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	18:56	105	110	32.004	33.528	1.524	19	Dry					
1184694	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	19:03	110	115	33.528	35.052	1.524	19	Dry					
1184695	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-19	19:09	115	120	35.052	36.576	1.524	19	Dry					
1184696	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	08:42	120	125	36.576	38.1	1.524	18	Dry					
1184697	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	09:29	125	130	38.1	39.624	1.524	19	Dry					
1184698	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	09:35	130	135	39.624	41.148	1.524	19	Dry					
1184699	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	09:41	135	140	41.148	42.672	1.524	19	Dry					
1184700	16QVV014	QVV	Corina Carlton CC02	Standard	2016-09-20	09:50			0	0	0							CDN-ME-1205
1184701	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	09:51	140	145	42.672	44.196	1.524	19	Dry					
1184702	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	09:57	145	150	44.196	45.72	1.524	19	Dry					
1184703	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:02	150	155	45.72	47.244	1.524	19	Dry					
1184704	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:08	155	160	47.244	48.768	1.524	19	Dry					
1184705	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:12	160	165	48.768	50.292	1.524	19	Dry					
1184706	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:18	165	170	50.292	51.816	1.524	19	Dry					
1184707	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:26	170	175	51.816	53.34	1.524	18	Dry					
1184708	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:35	175	180	53.34	54.864	1.524	19	Dry					
1184709	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:40	180	185	54.864	56.388	1.524	19	Dry					
1184710	16QVV014	QVV	Corina Carlton CC02	Standard	2016-09-20	10:45			0	0	0							CDN-GS-1K
1184711	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:47	185	190	56.388	57.912	1.524	19	Dry					
1184712	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	10:51	190	195	57.912	59.436	1.524	19	Dry					
1184713	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:00	195	200	59.436	60.96	1.524	19	Dry					
1184714	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:06	200	205	60.96	62.484	1.524	19	Dry					
1184715	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:16	205	210	62.484	64.008	1.524	19	Dry					
1184716	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:26	210	215	64.008	65.532	1.524	20	Dry					
1184717	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:35	215	220	65.532	67.056	1.524	20	Dry					
1184718	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:41	220	225	67.056	68.58	1.524	19	Dry					
1184719	16QVV014	QVV	Corina Carlton CC02	Sample	2016-09-20	11:50	225	230	68.58	70.104	1.524	20	Dry					

1184781	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	10:57	95	100	28.956	30.48	1.524	19							
1184782	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	11:28	100	105	30.48	32.004	1.524	18							
1184783	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	11:29	105	110	32.004	33.528	1.524	18							
1184784	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	11:56	110	115	33.528	35.052	1.524	18							
1184785	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	12:12	115	120	35.052	36.576	1.524	18							
1184786	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	12:24	120	125	36.576	38.1	1.524	19							
1184787	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	12:24	125	130	38.1	39.624	1.524	18							
1184788	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	13:26	130	135	39.624	41.148	1.524	18							
1184789	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	13:26	135	140	41.148	42.672	1.524	18							
1184790	16QVV016	QVV	Blake Mowbray BM03	Duplicate	2016-09-23	13:36	135	140	41.148	42.672	1.524	18						1184789	
1184791	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	13:36	140	145	42.672	44.196	1.524	19							
1184792	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	13:53	145	150	44.196	45.72	1.524	17							
1184793	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	14:00	150	155	45.72	47.244	1.524	18							
1184794	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	14:10	155	160	47.244	48.768	1.524	18							
1184795	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	14:59	160	165	48.768	50.292	1.524	19							
1184796	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	15:00	165	170	50.292	51.816	1.524	17							
1184797	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	15:00	170	175	51.816	53.34	1.524	18							
1184798	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	15:16	175	180	53.34	54.864	1.524	17							
1184799	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	16:01	180	185	54.864	56.388	1.524	17							
1184800	16QVV016	QVV	Blake Mowbray BM03	Standard	2016-09-23	16:02			0	0	0								CDN-ME-1205
1184801	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	16:19	185	190	56.388	57.912	1.524	17							
1184802	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	16:20	190	195	57.912	59.436	1.524	17							
1184803	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	16:47	195	200	59.436	60.96	1.524	18							
1184804	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	17:10	200	205	60.96	62.484	1.524	18							
1184805	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	17:30	205	210	62.484	64.008	1.524	18							
1184806	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	17:30	210	215	64.008	65.532	1.524	18							
1184807	16QVV016	QVV	Blake Mowbray BM03	Sample	2016-09-23	18:23	215	220	65.532	67.056	1.524	18							
1419601	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:49	0	5	0	1.524	1.524	15							
1419602	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:50	5	10	1.524	3.048	1.524	18							
1419603	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:50	10	15	3.048	4.572	1.524	20							
1419604	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:51	15	20	4.572	6.096	1.524	20							
1419605	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:51	20	25	6.096	7.62	1.524	20							
1419606	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:51	25	30	7.62	9.144	1.524	17						Open hole	
1419607	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:52	30	35	9.144	10.668	1.524	14							
1419608	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:52	35	40	10.668	12.192	1.524	16							
1419609	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:53	40	45	12.192	13.716	1.524	15							
1419610	16QVV017	QVV	Heidi Bradley HB04	Standard	2016-09-27	09:54			0	0	0								CDN-GS-1K
1419611	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:55	45	50	13.716	15.24	1.524	15							
1419612	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:56	50	55	15.24	16.764	1.524	15							
1419613	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:01	55	60	16.764	18.288	1.524	17							
1419614	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:02	60	65	18.288	19.812	1.524	18							
1419615	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:02	65	70	19.812	21.336	1.524	20							
1419616	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:03	70	75	21.336	22.86	1.524	20							
1419617	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:03	75	80	22.86	24.384	1.524	20							
1419618	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:03	80	85	24.384	25.908	1.524	18							
1419619	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:03	85	90	25.908	27.432	1.524	20							
1419620	16QVV017	QVV	Heidi Bradley HB04	Blank	2016-09-27	10:04			0	0	0							Coarse Blank	
1419621	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:05	90	95	27.432	28.956	1.524	20							
1419622	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:06	95	100	28.956	30.48	1.524	20							
1419623	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:06	100	105	30.48	32.004	1.524	20							
1419624	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:07	105	110	32.004	33.528	1.524	20							
1419625	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:07	110	115	33.528	35.052	1.524	20							
1419626	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:07	115	120	35.052	36.576	1.524	10							
1419627	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:07	120	125	36.576	38.1	1.524	20							
1419628	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:08	125	130	38.1	39.624	1.524	20							
1419629	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:08	130	135	39.624	41.148	1.524	20							
1419630	16QVV017	QVV	Heidi Bradley HB04	Duplicate	2016-09-27	10:09	130	135	39.624	41.148	1.524	20						1419629	
1419631	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:10	135	140	41.148	42.672	1.524	20							
1419632	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:22	140	145	42.672	44.196	1.524	20							
1419633	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:22	145	150	44.196	45.72	1.524	20							
1419634	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:22	150	155	45.72	47.244	1.524	20							
1419635	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:23	155	160	47.244	48.768	1.524	20							
1419636	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:23	160	165	48.768	50.292	1.524	20							
1419637	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:23	165	170	50.292	51.816	1.524	20							

1419638	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:24	170	175	51.816	53.34	1.524	20							
1419639	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:24	175	180	53.34	54.864	1.524	20							
1419640	16QVV017	QVV	Heidi Bradley HB04	Standard	2016-09-27	10:25			0	0	0								CDN-ME-1205
1419641	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:25	180	185	54.864	56.388	1.524	20							
1419642	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:26	185	190	56.388	57.912	1.524	20							
1419643	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:26	190	195	57.912	59.436	1.524	20							
1419644	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:26	195	200	59.436	60.96	1.524	20							
1419645	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:26	200	205	60.96	62.484	1.524	20							
1419646	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:27	205	210	62.484	64.008	1.524	20							
1419647	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:27	210	215	64.008	65.532	1.524	20							
1419648	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:27	215	220	65.532	67.056	1.524	20							
1419649	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	10:28	220	225	67.056	68.58	1.524	20							
1419650	16QVV017	QVV	Heidi Bradley HB04	Blank	2016-09-27	10:28			0	0	0								Coarse Blank
1419651	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:03	225	230	68.58	70.104	1.524	18							
1419652	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:03	230	235	70.104	71.628	1.524	18							
1419653	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:04	235	240	71.628	73.152	1.524	12							Mud ring loss of sample
1419654	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:04	240	245	73.152	74.676	1.524	20							
1419655	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:11	245	250	74.676	76.2	1.524	20							
1419656	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:11	250	255	76.2	77.724	1.524	20							
1419657	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:12	255	260	77.724	79.248	1.524	20							
1419658	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:12	260	265	79.248	80.772	1.524	20							
1419659	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:12	265	270	80.772	82.296	1.524	20							
1419660	16QVV017	QVV	Heidi Bradley HB04	Duplicate	2016-09-27	09:13	265	270	80.772	82.296	1.524	20							1419659
1419661	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:13	270	275	82.296	83.82	1.524	20							
1419662	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:14	275	280	83.82	85.344	1.524	20							
1419663	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:14	280	285	85.344	86.868	1.524	20							
1419664	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:14	285	290	86.868	88.392	1.524	20							
1419665	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:15	290	295	88.392	89.916	1.524	20							
1419666	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:15	295	300	89.916	91.44	1.524	20							
1419667	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:17	300	305	91.44	92.964	1.524	20							
1419668	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:17	305	310	92.964	94.488	1.524	20							
1419669	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:18	310	315	94.488	96.012	1.524	20							
1419670	16QVV017	QVV	Heidi Bradley HB04	Standard	2016-09-27	09:18			0	0	0								CDN-GS-1K
1419671	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:18	315	320	96.012	97.536	1.524	20							
1419672	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:19	320	325	97.536	99.06	1.524	20							
1419673	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:21	325	330	99.06	100.584	1.524	20							
1419674	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:21	330	335	100.584	102.108	1.524	20							
1419675	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	09:23	335	340	102.108	103.632	1.524	20							
1419676	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:26	340	345	103.632	105.156	1.524	20							
1419677	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:26	345	350	105.156	106.68	1.524	20							
1419678	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:27	350	355	106.68	108.204	1.524	10							
1419679	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:28	355	360	108.204	109.728	1.524	8							
1419680	16QVV017	QVV	Heidi Bradley HB04	Blank	2016-09-26	18:28			0	0	0								Coarse Blank
1419681	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:23	360	365	109.728	111.252	1.524	8							
1419682	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-26	18:43	365	370	111.252	112.776	1.524	7							
1419683	16QVV017	QVV	Heidi Bradley HB04	Sample	2016-09-27	11:49	370	375	112.776	114.3	1.524	20							Muddy!
1419684	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	14:44	0	5	0	1.524	1.524	20							
1419685	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	14:44	5	10	1.524	3.048	1.524	20							
1419686	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:10	10	15	3.048	4.572	1.524	20							
1419687	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:11	15	20	4.572	6.096	1.524	22							
1419688	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:11	20	25	6.096	7.62	1.524	18							Open hole
1419689	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:36	25	30	7.62	9.144	1.524	20							
1419690	16QVV018	QVV	Heidi Bradley HB04	Duplicate	2016-09-29	11:50	25	30	7.62	9.144	1.524	20							1419689
1419691	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:47	30	35	9.144	10.668	1.524	20							
1419692	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:48	35	40	10.668	12.192	1.524	20							
1419693	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:49	40	45	12.192	13.716	1.524	20							
1419694	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:55	45	50	13.716	15.24	1.524	20							
1419695	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:56	50	55	15.24	16.764	1.524	20							
1419696	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:56	55	60	16.764	18.288	1.524	18							
1419697	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:57	60	65	18.288	19.812	1.524	18							
1419698	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	15:57	65	70	19.812	21.336	1.524	20							
1419699	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:02	70	75	21.336	22.86	1.524	20							
1419700	16QVV018	QVV	Heidi Bradley HB04	Standard	2016-09-28	16:02			0	0	0								CDN-ME-1205
1419701	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:03	75	80	22.86	24.384	1.524	20							

1419702	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:10	80	85	24.384	25.908	1.524	20							
1419703	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:11	85	90	25.908	27.432	1.524	20							
1419704	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:11	90	95	27.432	28.956	1.524	20							
1419705	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:11	95	100	28.956	30.48	1.524	20							
1419706	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:12	100	105	30.48	32.004	1.524	20							
1419707	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:12	105	110	32.004	33.528	1.524	20							
1419708	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:13	110	115	33.528	35.052	1.524	20							
1419709	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:18	115	120	35.052	36.576	1.524	20							
1419710	16QVV018	QVV	Heidi Bradley HB04	Standard	2016-09-28	16:23			0	0	0								CDN-GS-1K
1419711	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:24	120	125	36.576	38.1	1.524	20							
1419712	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:24	125	130	38.1	39.624	1.524	20							
1419713	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:24	130	135	39.624	41.148	1.524	20							
1419714	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:25	135	140	41.148	42.672	1.524	20							
1419715	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:25	140	145	42.672	44.196	1.524	20							
1419716	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:25	145	150	44.196	45.72	1.524	20							
1419717	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:30	150	155	45.72	47.244	1.524	50							
1419718	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:30	155	160	47.244	48.768	1.524	20							
1419719	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:31	160	165	48.768	50.292	1.524	20							
1419720	16QVV018	QVV	Heidi Bradley HB04	Blank	2016-09-28	16:31			0	0	0								Coarse Blank
1419721	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:31	165	170	50.292	51.816	1.524	20							
1419722	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:32	170	175	51.816	53.34	1.524	20							
1419723	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:36	175	180	53.34	54.864	1.524	20							
1419724	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:37	180	185	54.864	56.388	1.524	20							
1419725	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:37	185	190	56.388	57.912	1.524	20							
1419726	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:38	190	195	57.912	59.436	1.524	20							
1419727	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:38	195	200	59.436	60.96	1.524	20							
1419728	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:38	200	205	60.96	62.484	1.524	20							
1419729	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:43	205	210	62.484	64.008	1.524	20							
1419730	16QVV018	QVV	Heidi Bradley HB04	Duplicate	2016-09-29	11:43	205	210	62.484	64.008	1.524	20							1419729
1419731	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:44	210	215	64.008	65.532	1.524	20							
1419732	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:44	215	220	65.532	67.056	1.524	20							
1419733	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:45	220	225	67.056	68.58	1.524	20							
1419734	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:45	225	230	68.58	70.104	1.524	20							
1419735	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:48	230	235	70.104	71.628	1.524	20							
1419736	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:49	235	240	71.628	73.152	1.524	20							
1419737	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	16:55	240	245	73.152	74.676	1.524	20							
1419738	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:00	245	250	74.676	76.2	1.524	20							
1419739	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:09	250	255	76.2	77.724	1.524	20							
1419740	16QVV018	QVV	Heidi Bradley HB04	Standard	2016-09-28	17:10			0	0	0								CDN-ME-1205
1419741	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:20	255	260	77.724	79.248	1.524	20							
1419742	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:27	260	265	79.248	80.772	1.524	20							
1419743	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:34	265	270	80.772	82.296	1.524	20							
1419744	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:39	270	275	82.296	83.82	1.524	20							
1419745	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:46	275	280	83.82	85.344	1.524	20							
1419746	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:51	280	285	85.344	86.868	1.524	20							
1419747	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	17:56	285	290	86.868	88.392	1.524	20							
1419748	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:05	290	295	88.392	89.916	1.524	20							
1419749	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:20	295	300	89.916	91.44	1.524	20							
1419750	16QVV018	QVV	Heidi Bradley HB04	Blank	2016-09-28	18:21			0	0	0								Coarse Blank
1456501	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:35	300	305	91.44	92.964	1.524	20							
1456502	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:35	305	310	92.964	94.488	1.524	20							
1456503	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:39	310	315	94.488	96.012	1.524	20							
1456504	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:43	315	320	96.012	97.536	1.524	10							
1456505	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-28	18:50	320	325	97.536	99.06	1.524	7							
1456506	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-29	15:02	325	330	99.06	100.584	1.524	20							Mostly water 1/4 cutting
1456507	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-29	15:13	330	335	100.584	102.108	1.524	20							Very musddy, mostly water 1/4 cutting
1456508	16QVV018	QVV	Heidi Bradley HB04	Sample	2016-09-29	15:21	335	340	102.108	103.632	1.524	10							Greasy sticky muck
1456509	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	14:57	0	5	0	1.524	1.524	20							
1456510	16QVV019	QVV	Heidi Bradley HB04	Standard	2016-09-30	16:06	40	45	12.192	13.716	1.524								CDN-GS-1K
1456511	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	16:06	5	10	1.524	3.048	1.524	18							
1456512	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	16:28	10	15	3.048	4.572	1.524	6							
1456513	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	16:43	15	20	4.572	6.096	1.524	18							
1456514	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	17:10	20	25	6.096	7.62	1.524	20							
1456515	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	18:04	25	30	7.62	9.144	1.524	18							

1456516	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	18:11	30	35	9.144	10.668	1.524	20						
1456517	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	18:18	35	40	10.668	12.192	1.524	20						
1456518	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	18:23	40	45	12.192	13.716	1.524	15						
1456519	16QVV019	QVV	Heidi Bradley HB04	Sample	2016-09-30	18:51	45	50	13.716	15.24	1.524	10						
1456520	16QVV019	QVV	Heidi Bradley HB04	Blank	2016-09-30	18:52			0	0	0							Coarse Blank
1456521	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-01	19:15	0	5	0	1.524	1.524	20						
1456522	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-01	19:20	5	10	1.524	3.048	1.524	20						
1456523	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-01	19:32	10	15	3.048	4.572	1.524	20						
1456524	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-01	19:41	15	20	4.572	6.096	1.524	20						
1456525	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-01	20:00	20	25	6.096	7.62	1.524	20						
1456526	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	09:51	25	30	7.62	9.144	1.524	20						
1456527	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	10:01	30	35	9.144	10.668	1.524	20						
1456528	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	10:14	35	40	10.668	12.192	1.524	20						
1456529	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	10:27	40	45	12.192	13.716	1.524	10						
1456530	16QVV020	QVV	Heidi Bradley HB04	Duplicate	2016-10-02	10:42	40	45	12.192	13.716	1.524	10					1456529	
1456531	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	10:42	45	50	13.716	15.24	1.524	20						
1456532	16QVV020	QVV	Heidi Bradley HB04	Sample	2016-10-02	11:50	50	55	15.24	16.764	1.524	12					Open hole sluffing still huge rock chips	
1456533	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:06	0	5	0	1.524	1.524	20						
1456534	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:08	5	10	1.524	3.048	1.524	17						
1456535	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:16	10	15	3.048	4.572	1.524	17						
1456536	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:28	15	20	4.572	6.096	1.524	16						
1456537	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:35	20	25	6.096	7.62	1.524	18						
1456538	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:42	25	30	7.62	9.144	1.524	20						
1456539	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	14:49	30	35	9.144	10.668	1.524	20						
1456540	16QVV021	QVV	Heidi Bradley HB04	Standard	2016-10-02	14:51			0	0	0							CDN-ME-1205
1456541	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	15:01	35	40	10.668	12.192	1.524	8						
1456542	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	15:13	40	45	12.192	13.716	1.524	16						
1456543	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	15:29	45	50	13.716	15.24	1.524	22						
1456544	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	16:12	50	55	15.24	16.764	1.524	20					Open hole	
1456545	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	16:27	55	60	16.764	18.288	1.524	20						
1456546	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	16:28	60	65	18.288	19.812	1.524	20						
1456547	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	17:18	65	70	19.812	21.336	1.524	20						
1456548	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	17:23	70	75	21.336	22.86	1.524	16						
1456549	16QVV021	QVV	Heidi Bradley HB04	Sample	2016-10-02	17:33	75	80	22.86	24.384	1.524	2					No analytical sample taken only drilled to 77ft hole sluffing. Still took XRF and chip sample	
1456550	16QVV022	QVV	Heidi Bradley HB04	Blank	2016-10-03	14:38			0	0	0							Coarse Blank
1456551	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	14:39	0	5	0	1.524	1.524	20						
1456552	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	14:41	5	10	1.524	3.048	1.524	20						
1456553	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	14:44	10	15	3.048	4.572	1.524	15						
1456554	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	14:45	15	20	4.572	6.096	1.524	10						
1456555	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	15:28	20	25	6.096	7.62	1.524	20						
1456556	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	15:39	25	30	7.62	9.144	1.524	20						
1456557	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	15:55	30	35	9.144	10.668	1.524	20						
1456558	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	16:06	35	40	10.668	12.192	1.524	20						
1456559	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	16:18	40	45	12.192	13.716	1.524	22						
1456560	16QVV022	QVV	Heidi Bradley HB04	Duplicate	2016-10-03	16:22	40	45	12.192	13.716	1.524	22						1456559
1456561	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	16:35	45	50	13.716	15.24	1.524	22						
1456562	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	17:44	50	55	15.24	16.764	1.524	15					Open hole	
1456563	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	17:50	55	60	16.764	18.288	1.524	16						
1456564	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	17:54	60	65	18.288	19.812	1.524	15						
1456565	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	17:59	65	70	19.812	21.336	1.524	7					Big chip chunks	
1456566	16QVV022	QVV	Heidi Bradley HB04	Sample	2016-10-03	18:05	70	75	21.336	22.86	1.524	4						
1456567	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	12:55	0	5	0	1.524	1.524	12						
1456568	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	13:46	5	10	1.524	3.048	1.524	16						
1456569	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	13:56	10	15	3.048	4.572	1.524	16						
1456570	16QVV023	QVV	Heidi Bradley HB04	Standard	2016-10-04	14:20			0	0	0							CDN-GS-1K
1456571	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	14:02	15	20	4.572	6.096	1.524	20						
1456572	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	14:12	20	25	6.096	7.62	1.524	20						
1456573	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	14:19	25	30	7.62	9.144	1.524	22						
1456574	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	14:34	30	35	9.144	10.668	1.524	20						
1456575	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	14:49	35	40	10.668	12.192	1.524	16						
1456576	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	15:06	40	45	12.192	13.716	1.524	17						
1456577	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	15:24	45	50	13.716	15.24	1.524	18						

1456578	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	16:05	50	55	15.24	16.764	1.524	12							
1456579	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	16:37	55	60	16.764	18.288	1.524	22							
1456580	16QVV023	QVV	Heidi Bradley HB04	Blank	2016-10-04	17:00			0	0	0								Coarse Blank
1456581	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	17:00	60	65	18.288	19.812	1.524	8							
1456582	16QVV023	QVV	Heidi Bradley HB04	Sample	2016-10-04	17:19	65	70	19.812	21.336	1.524	7							
1456583	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-05	19:14	0	5	0	1.524	1.524	20							
1456584	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	11:11	5	10	1.524	3.048	1.524	20							
1456585	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	12:03	10	15	3.048	4.572	1.524	23							
1456586	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	12:11	15	20	4.572	6.096	1.524	27							
1456587	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:05	20	25	6.096	7.62	1.524	18						Open hole	
1456588	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:06	25	30	7.62	9.144	1.524	20							
1456589	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:08	30	35	9.144	10.668	1.524	26							
1456590	16QVV024	QVV	Heidi Bradley HB04	Duplicate	2016-10-06	13:08	30	35	9.144	10.668	1.524	26						1456589	
1456591	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:11	35	40	10.668	12.192	1.524	26							
1456592	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:14	40	45	12.192	13.716	1.524	26							
1456593	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:19	45	50	13.716	15.24	1.524	26							
1456594	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:20	50	55	15.24	16.764	1.524	26							
1456595	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:27	55	60	16.764	18.288	1.524	24							
1456596	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:35	60	65	18.288	19.812	1.524	20							
1456597	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:42	65	70	19.812	21.336	1.524	20							
1456598	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:47	70	75	21.336	22.86	1.524	20							
1456599	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:51	75	80	22.86	24.384	1.524	20							
1456600	16QVV024	QVV	Heidi Bradley HB04	Standard	2016-10-06	13:52	0	0	0	0	0								CDN-ME-1205
1456601	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	13:55	80	85	24.384	25.908	1.524	20							
1456602	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	14:00	85	90	25.908	27.432	1.524	20							
1456603	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	14:05	90	95	27.432	28.956	1.524	20							
1456604	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	14:11	95	100	28.956	30.48	1.524	20							
1456605	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:06	100	105	30.48	32.004	1.524	20							
1456606	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:06	105	110	32.004	33.528	1.524	20							
1456607	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:14	110	115	33.528	35.052	1.524	20							
1456608	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:16	115	120	35.052	36.576	1.524	20							
1456609	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:18	120	125	36.576	38.1	1.524	20							
1456610	16QVV024	QVV	Heidi Bradley HB04	Standard	2016-10-06	15:20			0	0	0								CDN-GS-1K
1456611	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:24	125	130	38.1	39.624	1.524	20							
1456612	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:29	130	135	39.624	41.148	1.524	20							
1456613	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:30	135	140	41.148	42.672	1.524	20							
1456614	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:34	140	145	42.672	44.196	1.524	20							
1456615	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:38	145	150	44.196	45.72	1.524	20							
1456616	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:39	150	155	45.72	47.244	1.524	20							
1456617	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:43	155	160	47.244	48.768	1.524	20							
1456618	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:50	160	165	48.768	50.292	1.524	20							
1456619	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	15:55	165	170	50.292	51.816	1.524	20							
1456620	16QVV024	QVV	Heidi Bradley HB04	Blank	2016-10-06	15:55			0	0	0								Coarse Blank
1456621	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:01	170	175	51.816	53.34	1.524	20							
1456622	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:08	175	180	53.34	54.864	1.524	20							
1456623	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:15	180	185	54.864	56.388	1.524	20							
1456624	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:23	185	190	56.388	57.912	1.524	20							
1456625	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:30	190	195	57.912	59.436	1.524	20							
1456626	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:37	195	200	59.436	60.96	1.524	20							
1456627	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:44	200	205	60.96	62.484	1.524	20							
1456628	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:50	205	210	62.484	64.008	1.524	20							
1456629	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	16:56	210	215	64.008	65.532	1.524	20							
1456630	16QVV024	QVV	Heidi Bradley HB04	Duplicate	2016-10-06	16:57	210	215	64.008	65.532	1.524	20						1456629	
1456631	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:01	215	220	65.532	67.056	1.524	20							
1456632	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:08	220	225	67.056	68.58	1.524	20							
1456633	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:13	225	230	68.58	70.104	1.524	20							
1456634	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:19	230	235	70.104	71.628	1.524	20							
1456635	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:23	235	240	71.628	73.152	1.524	20							
1456636	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:31	240	245	73.152	74.676	1.524	20							
1456637	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:37	245	250	74.676	76.2	1.524	20							
1456638	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:43	250	255	76.2	77.724	1.524	20							
1456639	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:49	255	260	77.724	79.248	1.524	20							
1456640	16QVV024	QVV	Heidi Bradley HB04	Standard	2016-10-06	17:45			0	0	0								CDN-ME-1205
1456641	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	17:56	260	265	79.248	80.772	1.524	20							

1456642	16QVV024	QVV	Heidi Bradley HB04	Sample	2016-10-06	18:07	265	270	80.772	82.296	1.524	20						
1456643	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	4:27:00 PM	0	5	0	1.524	1.524	15	Dry					
1456644	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	4:36:00 PM	5	10	1.524	3.048	1.524	20	Dry					
1456645	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	4:36:00 PM	10	15	3.048	4.572	1.524	30	Dry					
1456646	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	4:53:00 PM	15	20	4.572	6.096	1.524	30	Dry					
1456647	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:13:00 PM	20	25	6.096	7.62	1.524	20	Dry					
1456648	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:16:00 PM	25	30	7.62	9.144	1.524	20	Dry					
1456649	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:26:00 PM	30	35	9.144	10.668	1.524	20	Dry					
1456650	16QVV025	QVV	Heidi Bradley HB04	Blank	2016-10-12	5:42:00 PM			0	0	0							Coarse Blank
1456651	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:26:00 PM	35	40	10.668	12.192	1.524	20	Dry					
1456652	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:30:00 PM	40	45	12.192	13.716	1.524	20	Dry					
1456653	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:34:00 PM	45	50	13.716	15.24	1.524	20	Dry					
1456654	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:35:00 PM	50	55	15.24	16.764	1.524	20	Dry					
1456655	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:42:00 PM	55	60	16.764	18.288	1.524	20	Dry					
1456656	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:45:00 PM	60	65	18.288	19.812	1.524	20	Dry					
1456657	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:51:00 PM	65	70	19.812	21.336	1.524	20	Dry					
1456658	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	5:59:00 PM	70	75	21.336	22.86	1.524	20	Dry					
1456659	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	6:01:00 PM	75	80	22.86	24.384	1.524	20	Dry					
1456660	16QVV025	QVV	Heidi Bradley HB04	Duplicate	2016-10-12	6:02:00 PM	75	80	22.86	24.384	1.524	20	Dry				1456659	
1456661	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	6:06:00 PM	80	85	24.384	25.908	1.524	20	Dry					
1456662	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	6:10:00 PM	85	90	25.908	27.432	1.524	20	Dry					
1456663	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	6:15:00 PM	90	95	27.432	28.956	1.524	20	Dry					
1456664	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-12	6:20:00 PM	95	100	28.956	30.48	1.524	20	Dry					
1456665	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:00:00 AM	100	105	30.48	32.004	1.524	20	Dry					
1456666	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:06:00 AM	105	110	32.004	33.528	1.524	20	Dry					
1456667	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:10:00 AM	110	115	33.528	35.052	1.524	20	Dry					
1456668	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:11:00 AM	115	120	35.052	36.576	1.524	20	Dry					
1456669	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:15:00 AM	120	125	36.576	38.1	1.524	20	Dry					
1456670	16QVV025	QVV	Heidi Bradley HB04	Standard	2016-10-13	11:33:00 AM			0	0	0							CDN-GS-1K
1456671	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:16:00 AM	125	130	38.1	39.624	1.524	20	Dry					
1456672	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:21:00 AM	130	135	39.624	41.148	1.524	20	Dry					
1456673	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:31:00 AM	135	140	41.148	42.672	1.524	20	Dry					
1456674	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:41:00 AM	140	145	42.672	44.196	1.524	20	Dry					
1456675	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	11:50:00 AM	145	150	44.196	45.72	1.524	20	Dry					
1456676	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:03:00 PM	150	155	45.72	47.244	1.524	20	Dry					
1456677	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:04:00 PM	155	160	47.244	48.768	1.524	20	Dry					
1456678	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:13:00 PM	160	165	48.768	50.292	1.524	20	Dry					
1456679	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:18:00 PM	165	170	50.292	51.816	1.524	20	Dry					
1456680	16QVV025	QVV	Heidi Bradley HB04	Blank	2016-10-13	12:26:00 PM			0	0	0							Coarse Blank
1456681	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:27:00 PM	170	175	51.816	53.34	1.524	20	Dry					
1456682	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:34:00 PM	175	180	53.34	54.864	1.524	20	Dry					
1456683	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	12:38:00 PM	180	185	54.864	56.388	1.524	20	Dry					
1456684	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	1:47:00 PM	185	190	56.388	57.912	1.524	20	Dry					
1456685	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	1:54:00 PM	190	195	57.912	59.436	1.524	20	Dry					
1456686	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:01:00 PM	195	200	59.436	60.96	1.524	20	Dry					
1456687	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:08:00 PM	200	205	60.96	62.484	1.524	20	Dry					
1456688	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:13:00 PM	205	210	62.484	64.008	1.524	20	Dry					
1456689	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:20:00 PM	210	215	64.008	65.532	1.524	20	Dry					
1456690	16QVV025	QVV	Heidi Bradley HB04	Duplicate	2016-10-13	2:21:00 PM	210	215	64.008	65.532	1.524	20	Dry				1456689	
1456691	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:25:00 PM	215	220	65.532	67.056	1.524	20	Dry					
1456692	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:29:00 PM	220	225	67.056	68.58	1.524	20	Dry					
1456693	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:38:00 PM	225	230	68.58	70.104	1.524	20	Dry					
1456694	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:45:00 PM	230	235	70.104	71.628	1.524	20	Dry					
1456695	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:52:00 PM	235	240	71.628	73.152	1.524	20	Dry					
1456696	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	2:59:00 PM	240	245	73.152	74.676	1.524	20	Dry					
1456697	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:06:00 PM	245	250	74.676	76.2	1.524	20	Dry					
1456698	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:17:00 PM	250	255	76.2	77.724	1.524	20	Dry					
1456699	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:25:00 PM	255	260	77.724	79.248	1.524	20	Dry					
1456700	16QVV025	QVV	Heidi Bradley HB04	Standard	2016-10-13	3:30:00 PM			0	0	0							CDN-GS-1K
1456701	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:31:00 PM	260	265	79.248	80.772	1.524	20	Dry					
1456702	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:37:00 PM	265	270	80.772	82.296	1.524	20	Dry					
1456703	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:43:00 PM	270	275	82.296	83.82	1.524	20	Dry					
1456704	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	3:52:00 PM	275	280	83.82	85.344	1.524	20	Dry					
1456705	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:02:00 PM	280	285	85.344	86.868	1.524	20	Dry					

1456706	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:09:00 PM	285	290	86.868	88.392	1.524		20	Dry				
1456707	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:15:00 PM	290	295	88.392	89.916	1.524		20	Dry				
1456708	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:27:00 PM	295	300	89.916	91.44	1.524		20	Dry				
1456709	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:38:00 PM	300	305	91.44	92.964	1.524		20	Dry				
1456710	16QVV025	QVV	Heidi Bradley HB04	Blank	2016-10-13	4:48:00 PM			0	0	0							Coarse Blank
1456711	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	4:48:00 PM	305	310	92.964	94.488	1.524		20	Dry				
1456712	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	5:00:00 PM	310	315	94.488	96.012	1.524		20	Dry				
1456713	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	5:06:00 PM	315	320	96.012	97.536	1.524		20	Dry				
1456714	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	5:16:00 PM	320	325	97.536	99.06	1.524		20	Dry				
1456715	16QVV025	QVV	Heidi Bradley HB04	Sample	2016-10-13	5:24:00 PM	325	330	99.06	100.584	1.524		20	Dry				
1456716	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	4:48:00 PM	0	5	0	1.524	1.524		35	Damp				
1456717	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	4:48:00 PM	5	10	1.524	3.048	1.524		25	Damp				
1456718	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:10:00 PM	10	15	3.048	4.572	1.524		28	Dry				
1456719	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:41:00 PM	15	20	4.572	6.096	1.524		20	Dry				
1456720	16QVV026	QVV	Heidi Bradley HB04	Blank	2016-10-14	5:12:00 PM			0	0	0							Coarse Blank
1456721	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:44:00 PM	20	25	6.096	7.62	1.524		20	Dry				
1456722	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:45:00 PM	25	30	7.62	9.144	1.524		20	Dry				
1456723	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:50:00 PM	30	35	9.144	10.668	1.524		20	Dry				
1456724	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:54:00 PM	35	40	10.668	12.192	1.524		20	Dry				
1456725	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	5:59:00 PM	40	45	12.192	13.716	1.524		20	Dry				
1456726	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	6:03:00 PM	45	50	13.716	15.24	1.524		20	Dry				
1456727	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	6:09:00 PM	50	55	15.24	16.764	1.524		20	Dry				
1456728	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	6:10:00 PM	55	60	16.764	18.288	1.524		20	Dry				
1456729	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	6:24:00 PM	60	65	18.288	19.812	1.524		20	Dry				
1456730	16QVV026	QVV	Heidi Bradley HB04	Duplicate	2016-10-14	6:24:00 PM	60	65	18.288	19.812	1.524		20	Dry			1456729	
1456731	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-14	6:32:00 PM	65	70	19.812	21.336	1.524		20	Dry				
1456732	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	12:54:00 PM	70	75	21.336	22.86	1.524		20	Dry				
1456733	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:06:00 PM	75	80	22.86	24.384	1.524		20	Dry				
1456734	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:12:00 PM	80	85	24.384	25.908	1.524		20	Dry				
1456735	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:17:00 PM	85	90	25.908	27.432	1.524		20	Dry				
1456736	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:22:00 PM	90	95	27.432	28.956	1.524		20	Dry				
1456737	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:33:00 PM	95	100	28.956	30.48	1.524		20	Dry				
1456738	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:33:00 PM	100	105	30.48	32.004	1.524		20	Dry				
1456739	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:45:00 PM	105	110	32.004	33.528	1.524		20	Dry				
1456740	16QVV026	QVV	Heidi Bradley HB04	Standard	2016-10-15	1:45:00 PM	130	135	39.624	41.148	1.524		20	Dry				CDN-ME-1205
1456741	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:46:00 PM	110	115	33.528	35.052	1.524		20	Dry	Weird fluffy? Maybe getting moisture?			
1456742	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:52:00 PM	115	120	35.052	36.576	1.524		20	Dry				
1456743	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	1:58:00 PM	120	125	36.576	38.1	1.524		20	Damp				
1456744	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:08:00 PM	125	130	38.1	39.624	1.524		15	Damp				
1456745	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:15:00 PM	130	135	39.624	41.148	1.524		15	Damp				
1456746	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:21:00 PM	135	140	41.148	42.672	1.524		14	Damp				
1456747	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:35:00 PM	140	145	42.672	44.196	1.524		10	Damp				
1456748	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:41:00 PM	145	150	44.196	45.72	1.524		18	Damp				
1456749	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	2:53:00 PM	150	155	45.72	47.244	1.524		10	Damp				
1456750	16QVV026	QVV	Heidi Bradley HB04	Blank	2016-10-15	2:54:00 PM			0	0	0						CDN-BL-10	CDN-BL-10
1456751	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	3:07:00 PM	155	160	47.244	48.768	1.524		20	Dry				
1456752	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	3:41:00 PM	160	165	48.768	50.292	1.524		5	Damp				
1456753	16QVV026	QVV	Heidi Bradley HB04	Sample	2016-10-15	3:47:00 PM	165	170	50.292	51.816	1.524		8	Wet				
1456754	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	3:33:00 PM	0	5	0	1.524	1.524		25	Damp				
1456755	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	4:00:00 PM	5	10	1.524	3.048	1.524		30	Damp				
1456756	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	4:24:00 PM	10	15	3.048	4.572	1.524		30	Dry				
1456757	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:01:00 PM	15	20	4.572	6.096	1.524		20	Dry	Open hole			
1456758	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:07:00 PM	20	25	6.096	7.62	1.524		20	Dry				
1456759	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:14:00 PM	25	30	7.62	9.144	1.524		20	Dry				
1456760	16QVV027	QVV	Heidi Bradley HB04	Duplicate	2016-10-16	5:15:00 PM	25	30	7.62	9.144	1.524		20	Dry			1456759	
1456761	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:19:00 PM	30	35	9.144	10.668	1.524		20	Dry				
1456762	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:23:00 PM	35	40	10.668	12.192	1.524		20	Dry				
1456763	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:29:00 PM	40	45	12.192	13.716	1.524		20	Dry				
1456764	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:35:00 PM	45	50	13.716	15.24	1.524		20	Dry				
1456765	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:41:00 PM	50	55	15.24	16.764	1.524		20	Dry				
1456766	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:45:00 PM	55	60	16.764	18.288	1.524		20	Dry				
1456767	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:51:00 PM	60	65	18.288	19.812	1.524		20	Dry				
1456768	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	5:58:00 PM	65	70	19.812	21.336	1.524		20	Dry				
1456769	16QVV027	QVV	Heidi Bradley HB04	Sample	2016-10-16	6:04:00 PM	70	75	21.336	22.86	1.524		20	Dry				

1456833	16QVV028	QVV	Heidi Bradley HB04	Sample	2016-10-19	3:53:00 PM	235	240	71.628	73.152	1.524		3	Wet	Split sample in half and put half in the analytical bag			
1456834	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:05:00 PM	0	5	0	1.524	1.524		17	Damp				
1456835	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:23:00 PM	5	10	1.524	3.048	1.524		15	Damp				
1456836	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:48:00 PM	10	15	3.048	4.572	1.524		20	Dry				
1456837	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:49:00 PM	15	20	4.572	6.096	1.524		20	Dry	Open hole			
1456838	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:53:00 PM	20	25	6.096	7.62	1.524		20	Dry				
1456839	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:53:00 PM	25	30	7.62	9.144	1.524		20	Dry				
1456840	16QVV029	QVV	Heidi Bradley HB04	Standard	2016-10-20	3:06:00 PM			0	0	0							CDN-ME-1205
1456841	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	2:57:00 PM	30	35	9.144	10.668	1.524		20	Dry				
1456842	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:02:00 PM	35	40	10.668	12.192	1.524		20	Dry				
1456843	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:07:00 PM	40	45	12.192	13.716	1.524		20	Dry				
1456844	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:10:00 PM	45	50	13.716	15.24	1.524		20	Dry				
1456845	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:14:00 PM	50	55	15.24	16.764	1.524		20	Dry				
1456846	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:19:00 PM	55	60	16.764	18.288	1.524		20	Dry				
1456847	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	3:59:00 PM	60	65	18.288	19.812	1.524		20	Dry				
1456848	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:03:00 PM	65	70	19.812	21.336	1.524		20	Dry				
1456849	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:07:00 PM	70	75	21.336	22.86	1.524		20	Dry				
1456850	16QVV029	QVV	Heidi Bradley HB04	Blank	2016-10-20	4:17:00 PM			0	0	0				CDN-BL-10			CDN-BL-10
1456851	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:17:00 PM	75	80	22.86	24.384	1.524		20	Dry				
1456852	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:18:00 PM	80	85	24.384	25.908	1.524		20	Dry				
1456853	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:18:00 PM	85	90	25.908	27.432	1.524		20	Dry				
1456854	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:39:00 PM	90	95	27.432	28.956	1.524		20	Dry				
1456855	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:45:00 PM	95	100	28.956	30.48	1.524		20	Dry				
1456856	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:51:00 PM	100	105	30.48	32.004	1.524		20	Dry				
1456857	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	4:58:00 PM	105	110	32.004	33.528	1.524		20	Dry				
1456858	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:03:00 PM	110	115	33.528	35.052	1.524		20	Dry				
1456859	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:10:00 PM	115	120	35.052	36.576	1.524		20	Dry				
1456860	16QVV029	QVV	Heidi Bradley HB04	Duplicate	2016-10-20	5:11:00 PM	115	120	35.052	36.576	1.524		20	Dry				1456859
1456861	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:16:00 PM	120	125	36.576	38.1	1.524		20	Dry				
1456862	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:23:00 PM	125	130	38.1	39.624	1.524		20	Dry				
1456863	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:28:00 PM	130	135	39.624	41.148	1.524		20	Dry				
1456864	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:33:00 PM	135	140	41.148	42.672	1.524		20	Dry				
1456865	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:39:00 PM	140	145	42.672	44.196	1.524		20	Dry				
1456866	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:45:00 PM	145	150	44.196	45.72	1.524		20	Dry				
1456867	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:50:00 PM	150	155	45.72	47.244	1.524		20	Dry				
1456868	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-20	5:56:00 PM	155	160	47.244	48.768	1.524		20	Dry				
1456869	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:03:00 PM	160	165	48.768	50.292	1.524		20	Dry				
1456870	16QVV029	QVV	Heidi Bradley HB04	Standard	2016-10-23	12:07:00 PM			0	0	0							CDN-GS-1K
1456871	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:08:00 PM	165	170	50.292	51.816	1.524		20	Damp				
1456872	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:14:00 PM	170	175	51.816	53.34	1.524		20	Damp				
1456873	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:15:00 PM	175	180	53.34	54.864	1.524		20	Damp				
1456874	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:19:00 PM	180	185	54.864	56.388	1.524		20	Damp				
1456875	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:20:00 PM	185	190	56.388	57.912	1.524		20	Damp				
1456876	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:22:00 PM	190	195	57.912	59.436	1.524		20	Damp				
1456877	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	12:28:00 PM	195	200	59.436	60.96	1.524		20	Damp				
1456878	16QVV029	QVV	Heidi Bradley HB04	Sample	2016-10-23	1:13:00 PM	200	205	60.96	62.484	1.524		20	Wet	Hit water, mixing of sample, possible contamination			
1456879	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	2:04:00 PM	0	5	0	1.524	1.524		18	Damp				
1456880	16QVV030	QVV	Heidi Bradley HB04	Blank	2016-10-24	2:17:00 PM			0	0	0				CDN-BL-10			CDN-BL-10
1456881	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	2:24:00 PM	5	10	1.524	3.048	1.524		20	Damp				
1456882	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	2:35:00 PM	10	15	3.048	4.572	1.524		20	Dry	Last casing			
1456883	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	3:08:00 PM	15	20	4.572	6.096	1.524		15	Dry				
1456884	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	3:27:00 PM	20	25	6.096	7.62	1.524		8	Dry	Hit a void? It was a really fast rod. Flushed nicely. Got stuck after first flush			
1456885	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-24	6:08:00 PM	25	30	7.62	9.144	1.524		20	Dry	Recase to the end of this rod			
1456886	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:05:00 PM	30	35	9.144	10.668	1.524		16	Dry	Open hole			
1456887	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:18:00 PM	35	40	10.668	12.192	1.524		15	Dry				
1456888	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:19:00 PM	40	45	12.192	13.716	1.524		15	Dry				
1456889	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:29:00 PM	45	50	13.716	15.24	1.524		15	Dry				
1456890	16QVV030	QVV	Heidi Bradley HB04	Duplicate	2016-10-25	12:29:00 PM	45	50	13.716	15.24	1.524		15	Dry				1456889
1456891	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:33:00 PM	50	55	15.24	16.764	1.524		20	Dry				
1456892	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:39:00 PM	55	60	16.764	18.288	1.524		20	Dry				

1456893	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:43:00 PM	60	65	18.288	19.812	1.524	20	Dry					
1456894	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:49:00 PM	65	70	19.812	21.336	1.524	20	Dry					
1456895	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:52:00 PM	70	75	21.336	22.86	1.524	20	Dry					
1456896	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	12:56:00 PM	75	80	22.86	24.384	1.524	15	Dry					
1456897	16QVV030	QVV	Heidi Bradley HB04	Sample	2016-10-25	1:01:00 PM	80	85	24.384	25.908	1.524	4	Dry					
1456898	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	3:54:00 PM	0	5	0	1.524	1.524	17	Damp					
1456899	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	3:59:00 PM	5	10	1.524	3.048	1.524	20	Damp					
1456900	16QVV031	QVV	Heidi Bradley HB04	Standard	2016-10-25	4:07:00 PM			0	0	0							CDN-ME-1205
1456901	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	4:08:00 PM	10	15	3.048	4.572	1.524	20	Damp					
1456902	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	4:16:00 PM	15	20	4.572	6.096	1.524	20	Dry					
1456903	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	4:37:00 PM	20	25	6.096	7.62	1.524	20	Dry					
1456904	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	4:38:00 PM	25	30	7.62	9.144	1.524	20	Dry					
1456905	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	4:59:00 PM	30	35	9.144	10.668	1.524	20	Dry					
1456906	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:02:00 PM	35	40	10.668	12.192	1.524	20	Dry					
1456907	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:05:00 PM	40	45	12.192	13.716	1.524	20	Dry					
1456908	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:11:00 PM	45	50	13.716	15.24	1.524	15	Dry					
1456909	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:16:00 PM	50	55	15.24	16.764	1.524	20	Dry					
1456910	16QVV031	QVV	Heidi Bradley HB04	Standard	2016-10-25	5:17:00 PM			0	0	0							CDN-GS-1K
1456911	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:19:00 PM	55	60	16.764	18.288	1.524	20	Dry					
1456912	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:24:00 PM	60	65	18.288	19.812	1.524	20	Dry					
1456913	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:37:00 PM	65	70	19.812	21.336	1.524	20	Dry					
1456914	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:43:00 PM	70	75	21.336	22.86	1.524	20	Dry					
1456915	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:46:00 PM	75	80	22.86	24.384	1.524	20	Dry					
1456916	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-25	5:50:00 PM	80	85	24.384	25.908	1.524	20	Dry					
1456917	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:16:00 AM	85	90	25.908	27.432	1.524	20	Dry					
1456918	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:20:00 AM	90	95	27.432	28.956	1.524	20	Dry					
1456919	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:27:00 AM	95	100	28.956	30.48	1.524	20	Dry					
1456920	16QVV031	QVV	Heidi Bradley HB04	Blank	2016-10-26	11:33:00 AM			0	0	0							CDN-BL-10
1456921	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:33:00 AM	100	105	30.48	32.004	1.524	20	Dry					CDN-BL-10
1456922	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:38:00 AM	105	110	32.004	33.528	1.524	20	Dry					
1456923	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:44:00 AM	110	115	33.528	35.052	1.524	20	Dry					
1456924	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:50:00 AM	115	120	35.052	36.576	1.524	20	Dry					
1456925	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	11:59:00 AM	120	125	36.576	38.1	1.524	20	Dry					
1456926	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	12:05:00 PM	125	130	38.1	39.624	1.524	20	Dry					
1456927	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	12:11:00 PM	130	135	39.624	41.148	1.524	20	Dry					
1456928	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	12:16:00 PM	135	140	41.148	42.672	1.524	20	Dry					
1456929	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	12:27:00 PM	140	145	42.672	44.196	1.524	20	Damp					
1456930	16QVV031	QVV	Heidi Bradley HB04	Duplicate	2016-10-26	1:02:00 PM	140	145	42.672	44.196	1.524	20	Damp					1456929
1456931	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	12:36:00 PM	145	150	44.196	45.72	1.524	6	Wet					
1456932	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	1:01:00 PM	150	155	45.72	47.244	1.524	15	Wet	Water				
1456933	16QVV031	QVV	Heidi Bradley HB04	Sample	2016-10-26	1:17:00 PM	155	160	47.244	48.768	1.524	15	Wet					
1456934	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	2:36:00 PM	0	5	0	1.524	1.524	20	Damp					
1456935	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	2:37:00 PM	5	10	1.524	3.048	1.524	20	Dry					
1456936	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	2:41:00 PM	10	15	3.048	4.572	1.524	22	Dry					
1456937	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	2:55:00 PM	15	20	4.572	6.096	1.524	22	Dry					
1456938	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	3:06:00 PM	20	25	6.096	7.62	1.524	22	Dry	Last casing				
1456939	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:06:00 PM	25	30	7.62	9.144	1.524	15	Dry	Open hole				
1456940	16QVV032	QVV	Heidi Bradley HB04	Standard	2016-10-27	4:07:00 PM			0	0	0							CDN-ME-1205
1456941	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:09:00 PM	30	35	9.144	10.668	1.524	20	Dry					
1456942	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:13:00 PM	35	40	10.668	12.192	1.524	20	Dry					
1456943	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:22:00 PM	40	45	12.192	13.716	1.524	20	Dry					
1456944	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:27:00 PM	45	50	13.716	15.24	1.524	20	Dry					
1456945	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:32:00 PM	50	55	15.24	16.764	1.524	20	Dry					
1456946	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:36:00 PM	55	60	16.764	18.288	1.524	20	Dry					
1456947	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:43:00 PM	60	65	18.288	19.812	1.524	20	Dry					
1456948	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:51:00 PM	65	70	19.812	21.336	1.524	20	Dry					
1456949	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:54:00 PM	70	75	21.336	22.86	1.524	20	Dry					
1456950	16QVV032	QVV	Heidi Bradley HB04	Blank	2016-10-27	4:58:00 PM			0	0	0							CDN-BL-10
1456951	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	4:59:00 PM	75	80	22.86	24.384	1.524	20	Dry					
1456952	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:03:00 PM	80	85	24.384	25.908	1.524	20	Dry					
1456953	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:06:00 PM	85	90	25.908	27.432	1.524	20	Dry					
1456954	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:11:00 PM	90	95	27.432	28.956	1.524	20	Dry					
1456955	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:15:00 PM	95	100	28.956	30.48	1.524	20	Dry					
1456956	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:30:00 PM	100	105	30.48	32.004	1.524	20	Dry					

1456957	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-27	5:39:00 PM	105	110	32.004	33.528	1.524	20	Dry					
1456958	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:10:00 AM	110	115	33.528	35.052	1.524	20	Dry					
1456959	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:16:00 AM	115	120	35.052	36.576	1.524	20	Dry					
1456960	16QVV032	QVV	Heidi Bradley HB04	Duplicate	2016-10-28	11:17:00 AM	115	120	35.052	36.576	1.524	20	Dry		1456959			
1456961	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:19:00 AM	120	125	36.576	38.1	1.524	20	Dry					
1456962	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:25:00 AM	125	130	38.1	39.624	1.524	20	Dry					
1456963	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:30:00 AM	130	135	39.624	41.148	1.524	20	Dry					
1456964	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:36:00 AM	135	140	41.148	42.672	1.524	20	Dry					
1456965	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:42:00 AM	140	145	42.672	44.196	1.524	20	Dry					
1456966	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:46:00 AM	145	150	44.196	45.72	1.524	20	Dry					
1456967	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:51:00 AM	150	155	45.72	47.244	1.524	20	Dry					
1456968	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	11:56:00 AM	155	160	47.244	48.768	1.524	20	Dry					
1456969	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:03:00 PM	160	165	48.768	50.292	1.524	20	Dry					
1456970	16QVV032	QVV	Heidi Bradley HB04	Standard	2016-10-28	12:04:00 PM			0	0	0							CDN-GS-1K
1456971	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:09:00 PM	165	170	50.292	51.816	1.524	20	Dry					
1456972	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:14:00 PM	170	175	51.816	53.34	1.524	20	Dry					
1456973	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:19:00 PM	175	180	53.34	54.864	1.524	20	Dry					
1456974	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:25:00 PM	180	185	54.864	56.388	1.524	20	Dry					
1456975	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:32:00 PM	185	190	56.388	57.912	1.524	20	Dry					
1456976	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:40:00 PM	190	195	57.912	59.436	1.524	20	Dry					
1456977	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:47:00 PM	195	200	59.436	60.96	1.524	20	Dry					
1456978	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	12:53:00 PM	200	205	60.96	62.484	1.524	20	Dry					
1456979	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:00:00 PM	205	210	62.484	64.008	1.524	20	Dry					
1456980	16QVV032	QVV	Heidi Bradley HB04	Blank	2016-10-28	1:01:00 PM			0	0	0				CDN-BL-10			CDN-BL-10
1456981	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:08:00 PM	210	215	64.008	65.532	1.524	20	Dry					
1456982	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:16:00 PM	215	220	65.532	67.056	1.524	20	Dry					
1456983	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:23:00 PM	220	225	67.056	68.58	1.524	20	Dry					
1456984	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:29:00 PM	225	230	68.58	70.104	1.524	20	Dry					
1456985	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:37:00 PM	230	235	70.104	71.628	1.524	20	Dry					
1456986	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:42:00 PM	235	240	71.628	73.152	1.524	20	Dry					
1456987	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:47:00 PM	240	245	73.152	74.676	1.524	20	Dry					
1456988	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:54:00 PM	245	250	74.676	76.2	1.524	20	Dry					
1456989	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	1:59:00 PM	250	255	76.2	77.724	1.524	20	Dry					
1456990	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:07:00 PM	255	260	77.724	79.248	1.524	20	Dry					
1456991	16QVV032	QVV	Heidi Bradley HB04	Duplicate	2016-10-28	2:07:00 PM	255	260	77.724	79.248	1.524	20	Dry		1456990			
1456992	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:12:00 PM	260	265	79.248	80.772	1.524	20	Dry					
1456993	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:19:00 PM	265	270	80.772	82.296	1.524	20	Dry					
1456994	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:29:00 PM	270	275	82.296	83.82	1.524	20	Dry					
1456995	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:54:00 PM	275	280	83.82	85.344	1.524	20	Dry					
1456996	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:54:00 PM	280	285	85.344	86.868	1.524	20	Dry					
1456997	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	2:55:00 PM	285	290	86.868	88.392	1.524	20	Dry					
1456998	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:00:00 PM	290	295	88.392	89.916	1.524	20	Dry					
1456999	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:08:00 PM	295	300	89.916	91.44	1.524	20	Dry					
1457000	16QVV032	QVV	Heidi Bradley HB04	Standard	2016-10-28	3:10:00 PM			0	0	0							CDN-GS-1K
1464001	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:16:00 PM	300	305	91.44	92.964	1.524	20	Dry					
1464002	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:22:00 PM	305	310	92.964	94.488	1.524	20	Dry					
1464003	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:29:00 PM	310	315	94.488	96.012	1.524	20	Dry					
1464004	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:34:00 PM	315	320	96.012	97.536	1.524	20	Dry					
1464005	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:39:00 PM	320	325	97.536	99.06	1.524	20	Dry					
1464006	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-10-28	3:45:00 PM	325	330	99.06	100.584	1.524	20	Dry					
1464007	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	11:53:00 AM	330	335	100.584	102.108	1.524	20	Damp					
1464008	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	11:57:00 AM	335	340	102.108	103.632	1.524	20	Damp					
1464009	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:02:00 PM	340	345	103.632	105.156	1.524	20	Dry					
1464010	16QVV032	QVV	Heidi Bradley HB04	Standard	2016-11-02	12:08:00 PM			0	0	0							CDN-GS-1K
1464011	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:09:00 PM	345	350	105.156	106.68	1.524	20	Dry					
1464012	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:16:00 PM	350	355	106.68	108.204	1.524	20	Dry					
1464013	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:22:00 PM	355	360	108.204	109.728	1.524	20	Dry					
1464014	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:29:00 PM	360	365	109.728	111.252	1.524	20	Dry					
1464015	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:35:00 PM	365	370	111.252	112.776	1.524	20	Dry					
1464016	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:41:00 PM	370	375	112.776	114.3	1.524	20	Dry					
1464017	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:47:00 PM	375	380	114.3	115.824	1.524	20	Dry					
1464018	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	12:54:00 PM	380	385	115.824	117.348	1.524	20	Dry					
1464019	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:00:00 PM	385	390	117.348	118.872	1.524	20	Dry					
1464020	16QVV032	QVV	Heidi Bradley HB04	Blank	2016-11-02	1:01:00 PM			0	0	0				CDN-BL-10			CDN-BL-10

1464021	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:09:00 PM	390	395	118.872	120.396	1.524	20	Dry					
1464022	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:16:00 PM	395	400	120.396	121.92	1.524	20	Dry					
1464023	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:30:00 PM	400	405	121.92	123.444	1.524	20	Dry					
1464024	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:34:00 PM	405	410	123.444	124.968	1.524	20	Dry					
1464025	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:46:00 PM	410	415	124.968	126.492	1.524	20	Dry					
1464026	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:51:00 PM	415	420	126.492	128.016	1.524	20	Dry					
1464027	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	1:58:00 PM	420	425	128.016	129.54	1.524	20	Dry					
1464028	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:04:00 PM	425	430	129.54	131.064	1.524	20	Dry					
1464029	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:16:00 PM	430	435	131.064	132.588	1.524	20	Dry	1464030 is the dupe of this sample				
1464030	16QVV032	QVV	Heidi Bradley HB04	Duplicate	2016-11-02	2:16:00 PM												
1464031	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:21:00 PM	435	440	132.588	134.112	1.524	20	Dry					
1464032	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:30:00 PM	440	445	134.112	135.636	1.524	20	Dry					
1464033	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:37:00 PM	445	450	135.636	137.16	1.524	20	Dry					
1464034	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:44:00 PM	450	455	137.16	138.684	1.524	20	Dry		20			
1464035	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	2:53:00 PM	455	460	138.684	140.208	1.524	20	Dry					
1464036	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	3:01:00 PM	460	465	140.208	141.732	1.524	20	Dry					
1464037	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	3:07:00 PM	465	470	141.732	143.256	1.524	20	Dry					
1464038	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	3:15:00 PM	475	475	143.256	144.78	1.524	20	Dry					
1464039	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	3:23:00 PM	475	480	144.78	146.304	1.524	20	Dry					
1464040	16QVV032	QVV	Heidi Bradley HB04	Standard	2016-11-02	3:24:00 PM			0	0	0							CDN-ME-1205
1464041	16QVV032	QVV	Heidi Bradley HB04	Sample	2016-11-02	3:24:00 PM	480	485	146.304	147.828	1.524	20	Dry					
1464042	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	1:21:00 PM	0	5	0	1.524	1.524	15	Damp					
1464043	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	1:25:00 PM	5	10	1.524	3.048	1.524	20	Dry					
1464044	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	1:34:00 PM	10	15	3.048	4.572	1.524	20	Dry					
1464045	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	1:46:00 PM	15	20	4.572	6.096	1.524	22	Dry					
1464046	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	2:05:00 PM	20	25	6.096	7.62	1.524	20	Dry					
1464047	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	2:09:00 PM	25	30	7.62	9.144	1.524	20	Dry					
1464048	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	2:12:00 PM	30	35	9.144	10.668	1.524	20	Dry					
1464049	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	2:16:00 PM	35	40	10.668	12.192	1.524	20	Dry					
1464050	16QVV033	QVV	Heidi Bradley HB04	Blank	2016-11-03	2:17:00 PM			0	0	0			CDN-BL-10				CDN-BL-10
1464051	16QVV033	QVV	Heidi Bradley HB04	Sample	2016-11-03	2:19:00 PM	40	45	12.192	13.716	1.524	12	Dry					
1464052	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-03	4:26:00 PM	0	5	0	1.524	1.524	15	Dry					
1464053	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-03	4:35:00 PM	5	10	1.524	3.048	1.524	20	Dry					
1464054	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-03	4:46:00 PM	10	15	3.048	4.572	1.524	20	Dry					
1464055	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-03	4:54:00 PM	15	20	4.572	6.096	1.524	20	Dry					
1464056	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	10:58:00 AM	20	25	6.096	7.62	1.524	15	Damp	Big rocks				
1464057	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	10:59:00 AM	25	30	7.62	9.144	1.524	15	Damp	Big rocks				
1464058	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:02:00 AM	30	35	9.144	10.668	1.524	20	Dry	Big rocks				
1464059	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:04:00 AM	35	40	10.668	12.192	1.524	20	Dry					
1464060	16QVV034	QVV	Heidi Bradley HB04	Duplicate	2016-11-07	11:05:00 AM	35	40	10.668	12.192	1.524	20	Dry					1464059
1464061	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:07:00 AM	40	45	12.192	13.716	1.524	20	Dry					
1464062	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:11:00 AM	45	50	13.716	15.24	1.524	20	Dry					
1464063	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:17:00 AM	50	55	15.24	16.764	1.524	20	Dry					
1464064	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:21:00 AM	55	60	16.764	18.288	1.524	20	Dry					
1464065	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:25:00 AM	60	65	18.288	19.812	1.524	20	Damp					
1464066	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:32:00 AM	65	70	19.812	21.336	1.524	20	Dry					
1464067	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:37:00 AM	70	75	21.336	22.86	1.524	20	Dry	Big rocks				
1464068	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:41:00 AM	75	80	22.86	24.384	1.524	20	Dry					
1464069	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:47:00 AM	80	85	24.384	25.908	1.524	20	Dry					
1464070	16QVV034	QVV	Heidi Bradley HB04	Standard	2016-11-07	11:47:00 AM			0	0	0							CDN-GS-1K
1464071	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:51:00 AM	85	90	25.908	27.432	1.524	20	Dry					
1464072	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	11:55:00 AM	90	95	27.432	28.956	1.524	20	Dry					
1464073	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:04:00 PM	95	100	28.956	30.48	1.524	20	Dry					
1464074	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:07:00 PM	100	105	30.48	32.004	1.524	20	Dry					
1464075	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:15:00 PM	105	110	32.004	33.528	1.524	20	Dry					
1464076	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:22:00 PM	110	115	33.528	35.052	1.524	20	Dry					
1464077	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:27:00 PM	115	120	35.052	36.576	1.524	20	Dry					
1464078	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:33:00 PM	120	125	36.576	38.1	1.524	20	Dry					
1464079	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:39:00 PM	125	130	38.1	39.624	1.524	20	Dry					
1464080	16QVV034	QVV	Heidi Bradley HB04	Blank	2016-11-07	12:40:00 PM			0	0	0			CDN-BL-10				CDN-BL-10
1464081	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	12:45:00 PM	130	135	39.624	41.148	1.524	20	Dry					
1464082	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	1:39:00 PM	135	140	41.148	42.672	1.524	20	Dry					
1464083	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	1:44:00 PM	140	145	42.672	44.196	1.524	20	Dry					
1464084	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	1:51:00 PM	145	150	44.196	45.72	1.524	20	Dry					

1464085	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	1:58:00 PM	150	155	45.72	47.244	1.524	20	Dry					
1464086	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:01:00 PM	155	160	47.244	48.768	1.524	20	Dry					
1464087	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:09:00 PM	160	165	48.768	50.292	1.524	20	Dry					
1464088	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:13:00 PM	165	170	50.292	51.816	1.524	20	Dry					
1464089	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:21:00 PM	170	175	51.816	53.34	1.524	20	Dry					
1464090	16QVV034	QVV	Heidi Bradley HB04	Duplicate	2016-11-07	2:21:00 PM	170	175	51.816	53.34	1.524	20	Dry				1464089	
1464091	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:27:00 PM	175	180	53.34	54.864	1.524	20	Dry				20	
1464092	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:30:00 PM	180	185	54.864	56.388	1.524	20	Dry					
1464093	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:37:00 PM	185	190	56.388	57.912	1.524	20	Dry					
1464094	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:43:00 PM	190	195	57.912	59.436	1.524	20	Dry					
1464095	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-07	2:49:00 PM	195	200	59.436	60.96	1.524	20	Dry					
1464096	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	10:25:00 AM	200	205	60.96	62.484	1.524	20	Dry					
1464097	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	10:34:00 AM	205	210	62.484	64.008	1.524	8	Damp					
1464098	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	10:43:00 AM	210	215	64.008	65.532	1.524	15	Damp					
1464099	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	10:50:00 AM	215	220	65.532	67.056	1.524	20	Damp					
1464100	16QVV034	QVV	Heidi Bradley HB04	Standard	2016-11-08	10:51:00 AM			0	0	0							CDN-ME-1205
1464101	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	10:55:00 AM	220	225	67.056	68.58	1.524	20	Damp					
1464102	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:00:00 AM	225	230	68.58	70.104	1.524	20	Dry					
1464103	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:20:00 AM	230	235	70.104	71.628	1.524	20	Damp					
1464104	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:24:00 AM	235	240	71.628	73.152	1.524	20	Damp					
1464105	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:31:00 AM	240	245	73.152	74.676	1.524	20	Damp					
1464106	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:36:00 AM	245	250	74.676	76.2	1.524	20	Dry					
1464107	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:42:00 AM	250	255	76.2	77.724	1.524	20	Dry					
1464108	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:49:00 AM	255	260	77.724	79.248	1.524	20	Dry					
1464109	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	11:55:00 AM	260	265	79.248	80.772	1.524	20	Damp					
1464110	16QVV034	QVV	Heidi Bradley HB04	Standard	2016-11-08	11:50:00 AM			0	0	0							CDN-GS-1K
1464111	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:01:00 PM	265	270	80.772	82.296	1.524	20	Damp					
1464112	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:07:00 PM	270	275	82.296	83.82	1.524	20	Dry					
1464113	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:15:00 PM	275	280	83.82	85.344	1.524	20	Damp					
1464114	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:22:00 PM	280	285	85.344	86.868	1.524	20	Damp					
1464115	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:30:00 PM	285	290	86.868	88.392	1.524	20	Damp					
1464116	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:35:00 PM	290	295	88.392	89.916	1.524	20	Damp					
1464117	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:43:00 PM	295	300	89.916	91.44	1.524	20	Damp					
1464118	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:48:00 PM	300	305	91.44	92.964	1.524	20	Damp					
1464119	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	12:54:00 PM	305	310	92.964	94.488	1.524	20	Dry					
1464120	16QVV034	QVV	Heidi Bradley HB04	Blank	2016-11-08	12:54:00 PM			0	0	0						CDN-BL-10	CDN-BL-10
1464121	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:01:00 PM	310	315	94.488	96.012	1.524	20	Dry					
1464122	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:08:00 PM	315	320	96.012	97.536	1.524	20	Dry					
1464123	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:12:00 PM	320	325	97.536	99.06	1.524	20	Dry					
1464124	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:20:00 PM	325	330	99.06	100.584	1.524	20	Dry					
1464125	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:26:00 PM	330	335	100.584	102.108	1.524	20	Dry					
1464126	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:34:00 PM	335	340	102.108	103.632	1.524	20	Dry					
1464127	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:39:00 PM	340	345	103.632	105.156	1.524	20	Dry					
1464128	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:46:00 PM	345	350	105.156	106.68	1.524	20	Dry					
1464129	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	1:56:00 PM	350	355	106.68	108.204	1.524	20	Dry					
1464130	16QVV034	QVV	Heidi Bradley HB04	Duplicate	2016-11-08	1:56:00 PM	350	355	106.68	108.204	1.524	20	Dry					1464129
1464131	16QVV034	QVV	Heidi Bradley HB04	Sample	2016-11-08	2:03:00 PM	355	360	108.204	109.728	1.524	20	Dry				EOH	

Appendix E: RAB Assay Certificates



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 06, 2016
Report Date: September 21, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000258.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-02-Rock
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419001	Rock	1.46	0.009	4.3	15.5	13.3	51	<0.1	16.8	4.8	728	2.44	48.6	3.7	10.7	74	0.3	5.4	0.2	23	0.20
1419002	Rock	2.29	<0.005	3.0	12.1	10.5	37	<0.1	3.9	3.9	403	2.62	12.6	0.5	7.1	99	0.1	3.3	0.4	9	0.08
1419003	Rock	2.05	0.007	1.7	8.2	22.5	38	<0.1	2.6	2.4	407	1.69	19.2	<0.5	11.6	134	0.3	2.6	0.2	15	0.07
1419004	Rock	2.48	8.249	4.0	10.1	995.8	69	24.3	1.8	2.0	222	1.86	895.5	6759.3	9.2	187	1.4	38.8	12.0	6	0.07
1419005	Rock	2.75	7.332	3.3	74.0	1027.5	116	27.0	1.9	1.7	430	2.28	4001.8	7643.4	11.4	211	5.2	104.1	15.0	17	0.18
1419006	Rock	2.32	0.242	2.7	11.9	41.3	108	0.5	1.9	2.4	847	3.26	1133.9	237.8	14.9	114	1.0	23.2	0.2	45	0.17
1419007	Rock	2.69	0.074	1.8	6.2	18.8	50	0.2	1.7	3.1	800	2.65	128.6	70.5	19.5	126	0.4	4.6	0.2	40	0.12
1419008	Rock	2.59	0.095	1.2	4.0	19.6	66	0.2	4.6	3.7	864	2.53	33.9	87.4	16.7	144	0.4	3.0	0.2	52	2.51
1419009	Rock	2.33	0.031	2.5	5.6	14.0	43	0.1	5.9	6.2	975	2.08	21.2	35.5	12.5	85	<0.1	2.1	0.2	16	1.15
1419010	Rock Pulp	0.12	0.803	4.3	32.0	4.9	53	0.3	24.1	9.2	401	2.58	7.3	1445.0	0.9	43	0.1	1.0	<0.1	60	0.84
1419011	Rock	2.06	0.038	2.6	7.2	15.6	38	<0.1	3.1	3.1	483	1.91	12.0	36.6	15.6	72	<0.1	4.2	0.3	19	0.12
1419012	Rock	2.36	0.040	1.7	9.0	10.5	31	0.1	3.0	1.8	355	1.24	12.5	57.1	5.1	89	0.1	3.9	0.1	26	0.28
1419013	Rock	2.25	0.040	1.4	7.3	8.1	33	<0.1	2.7	2.6	416	1.57	8.6	18.9	8.9	81	0.2	3.0	0.2	21	0.76
1419014	Rock	2.63	0.021	2.9	10.6	13.3	35	<0.1	2.6	4.0	507	2.21	13.7	17.1	13.2	72	<0.1	3.3	0.2	13	1.14
1419015	Rock	2.36	0.006	3.3	10.8	10.4	54	<0.1	7.8	11.2	791	3.88	8.5	6.2	10.1	93	0.1	2.3	0.2	44	1.91
1419016	Rock	2.35	0.017	2.5	6.6	9.7	42	<0.1	2.6	3.5	524	2.29	9.8	10.5	18.4	44	<0.1	1.5	0.2	15	0.32
1419017	Rock	2.65	0.010	2.0	8.6	8.0	32	<0.1	1.9	3.9	488	2.31	6.1	10.0	16.5	43	<0.1	0.7	0.2	12	0.45
1419018	Rock	2.50	0.018	4.8	8.3	6.6	22	<0.1	1.8	3.3	309	2.07	5.6	10.2	14.2	42	<0.1	0.5	0.2	11	0.30
1419019	Rock	2.47	0.020	46.6	20.6	10.2	34	0.1	2.9	4.6	432	2.34	6.4	22.6	13.9	68	0.2	1.2	0.3	15	0.64
1419020	Rock	0.59	<0.005	0.1	2.6	1.4	16	<0.1	1.2	0.9	236	0.50	<0.5	2.3	0.1	51	0.2	<0.1	<0.1	<2	20.63
1419021	Rock	2.31	0.010	10.3	28.0	9.2	37	<0.1	1.7	4.2	470	2.59	18.4	6.2	13.7	54	0.1	1.6	0.4	12	0.44
1419022	Rock	2.52	<0.005	2.4	25.6	4.0	58	<0.1	35.3	15.8	670	3.28	5.2	4.7	5.7	87	0.1	0.3	0.1	81	1.72
1419023	Rock	2.41	0.009	5.2	55.2	10.1	40	0.1	3.2	5.6	438	2.87	68.1	11.9	16.5	36	<0.1	2.2	0.3	16	0.20
1419024	Rock	2.60	0.011	2.6	21.2	6.7	58	<0.1	19.7	10.7	774	2.72	10.1	4.8	14.3	64	<0.1	0.9	0.1	50	1.74
1419025	Rock	2.82	0.008	4.8	17.5	5.0	51	<0.1	4.9	6.3	578	2.68	7.0	2.9	10.5	35	<0.1	0.3	<0.1	33	0.58
1419026	Rock	2.91	0.010	4.7	16.3	4.4	50	<0.1	7.1	7.2	584	2.68	9.1	6.9	10.1	39	<0.1	0.4	0.2	37	1.00
1419027	Rock	2.76	0.006	2.1	20.6	5.9	59	<0.1	6.5	6.3	616	2.56	5.5	1.6	14.1	110	0.2	0.4	0.2	28	1.11
1419028	Rock	2.70	<0.005	2.1	27.6	7.1	43	<0.1	12.6	7.5	544	2.28	2.9	4.3	11.1	195	0.1	0.3	0.2	31	1.99
1419029	Rock	2.76	0.006	1.4	13.0	6.0	57	<0.1	23.8	9.7	631	2.49	2.3	7.0	5.1	128	0.2	0.2	<0.1	59	1.49
1419030	Rock	1.70	0.006	1.6	13.5	6.0	60	<0.1	22.8	9.6	624	2.49	2.0	<0.5	5.4	128	<0.1	0.2	<0.1	59	1.52



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1419001	Rock	0.021	19	15	0.07	2132	0.004	31	0.43	0.066	0.18	1.1	0.26	5.5	0.1	0.06	2	<0.5	<0.2
1419002	Rock	0.009	11	4	0.06	2940	<0.001	<20	0.50	0.039	0.25	0.6	0.13	4.8	0.1	0.07	2	<0.5	<0.2
1419003	Rock	0.016	15	3	0.03	3326	<0.001	<20	0.32	0.086	0.12	1.2	0.72	4.5	0.1	0.08	<1	<0.5	<0.2
1419004	Rock	0.007	19	2	0.02	3575	<0.001	<20	0.39	0.043	0.22	0.9	1.26	3.1	0.9	0.18	1	3.5	16.0
1419005	Rock	0.014	19	2	0.03	3893	<0.001	<20	0.52	0.018	0.31	2.3	4.16	4.3	3.9	0.17	1	2.1	13.5
1419006	Rock	0.048	31	3	0.03	2443	<0.001	<20	0.49	0.074	0.22	3.0	2.10	5.6	1.4	0.06	1	1.0	0.4
1419007	Rock	0.045	36	3	0.03	3494	0.001	<20	0.35	0.132	0.11	1.4	0.51	5.1	0.2	0.08	1	0.8	<0.2
1419008	Rock	0.056	26	9	0.09	2934	0.008	<20	0.27	0.112	0.10	0.6	0.32	7.5	0.1	0.06	<1	<0.5	<0.2
1419009	Rock	0.036	17	10	0.09	1085	0.004	<20	0.54	0.040	0.31	0.3	0.28	5.6	0.3	<0.05	2	<0.5	<0.2
1419010	Rock Pulp	0.055	4	31	0.77	102	0.115	<20	1.55	0.089	0.14	11.4	0.06	4.8	<0.1	<0.05	5	<0.5	<0.2
1419011	Rock	0.031	26	5	0.05	1992	0.010	<20	0.35	0.088	0.19	0.3	0.25	3.7	0.1	<0.05	2	<0.5	<0.2
1419012	Rock	0.012	10	5	0.02	1087	0.001	21	0.22	0.060	0.17	0.4	0.32	2.4	<0.1	<0.05	<1	<0.5	<0.2
1419013	Rock	0.029	17	4	0.05	686	0.005	<20	0.39	0.060	0.26	0.3	0.20	2.4	0.1	<0.05	2	<0.5	<0.2
1419014	Rock	0.035	27	5	0.08	757	0.005	<20	0.47	0.054	0.28	0.3	0.09	3.9	0.2	<0.05	2	1.3	<0.2
1419015	Rock	0.085	25	13	0.19	1190	0.015	<20	0.80	0.034	0.54	0.2	0.14	12.0	0.3	<0.05	4	<0.5	<0.2
1419016	Rock	0.047	43	7	0.35	454	0.060	<20	0.82	0.063	0.63	0.4	0.04	3.3	0.4	<0.05	5	<0.5	<0.2
1419017	Rock	0.044	44	6	0.34	338	0.067	<20	0.83	0.076	0.58	1.0	0.01	2.5	0.3	<0.05	5	0.6	<0.2
1419018	Rock	0.038	30	6	0.32	244	0.076	<20	0.69	0.076	0.40	2.8	<0.01	1.9	0.2	0.25	4	<0.5	<0.2
1419019	Rock	0.048	37	7	0.23	985	0.034	<20	0.59	0.067	0.40	1.4	0.08	3.4	0.2	<0.05	3	0.9	0.3
1419020	Rock	0.014	<1	<1	11.25	14	<0.001	<20	0.01	0.002	<0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1419021	Rock	0.056	37	4	0.33	281	0.057	<20	0.78	0.070	0.49	0.7	0.10	2.7	0.2	0.05	5	0.7	<0.2
1419022	Rock	0.107	20	90	1.73	363	0.208	<20	1.80	0.074	1.25	0.4	<0.01	6.5	0.6	<0.05	7	<0.5	<0.2
1419023	Rock	0.050	43	7	0.28	326	0.023	<20	0.90	0.071	0.27	0.5	0.03	3.3	0.1	<0.05	5	0.6	<0.2
1419024	Rock	0.064	30	27	0.95	178	0.156	<20	1.36	0.064	0.96	0.4	<0.01	5.2	0.5	<0.05	6	<0.5	<0.2
1419025	Rock	0.066	35	10	0.78	216	0.155	<20	1.34	0.085	0.89	2.7	0.03	2.7	0.4	0.29	7	1.0	<0.2
1419026	Rock	0.063	32	13	0.80	172	0.105	<20	1.20	0.054	0.78	2.3	0.01	3.2	0.3	0.36	7	1.0	<0.2
1419027	Rock	0.064	40	12	0.55	777	0.080	<20	0.88	0.077	0.49	3.0	<0.01	3.4	0.2	0.51	6	<0.5	<0.2
1419028	Rock	0.050	33	17	0.58	1087	0.065	<20	0.75	0.067	0.48	2.3	<0.01	3.7	0.3	0.34	4	<0.5	<0.2
1419029	Rock	0.074	16	29	0.95	238	0.158	<20	1.10	0.081	0.87	1.5	<0.01	5.0	0.4	<0.05	6	<0.5	<0.2
1419030	Rock	0.072	16	29	0.94	244	0.160	<20	1.08	0.081	0.87	1.5	<0.01	4.7	0.4	<0.05	6	0.9	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419031	Rock	2.86	0.006	2.1	21.4	3.7	41	<0.1	20.4	10.9	492	2.73	3.5	2.2	8.2	51	<0.1	0.2	<0.1	45	1.26
1419032	Rock	2.80	0.011	3.1	8.3	5.8	27	<0.1	2.2	4.1	327	2.17	3.1	7.4	12.0	85	<0.1	0.3	<0.1	15	1.02
1419033	Rock	3.14	<0.005	3.5	21.1	6.0	47	<0.1	1.6	4.2	485	2.31	3.6	4.1	9.9	224	0.1	0.3	<0.1	13	1.41
1419034	Rock	2.59	0.006	2.3	20.1	5.4	35	<0.1	2.1	3.3	450	1.83	3.5	6.7	9.2	151	<0.1	0.3	<0.1	10	1.43
1419035	Rock	2.44	<0.005	2.8	18.1	4.8	32	<0.1	8.3	5.5	362	1.73	2.8	3.0	20.4	92	<0.1	0.2	<0.1	20	0.80
1419036	Rock	2.89	<0.005	2.2	26.6	8.2	47	<0.1	2.5	5.9	710	2.49	3.8	3.3	11.7	372	0.1	0.3	<0.1	33	2.26
1419037	Rock	2.57	0.006	2.0	32.7	4.4	44	<0.1	3.2	4.9	532	2.42	2.9	2.3	13.4	151	0.1	0.2	<0.1	31	1.30
1419038	Rock	2.71	0.007	2.7	9.4	4.4	38	<0.1	2.3	3.5	433	1.98	3.7	6.3	14.2	42	<0.1	0.2	<0.1	14	0.70
1419039	Rock	2.97	<0.005	2.9	8.1	3.6	52	<0.1	31.1	12.8	711	2.48	2.7	<0.5	9.5	106	<0.1	0.1	<0.1	49	2.51
1419040	Rock Pulp	0.12	1.975	55.1	2185.5	1269.3	3672	25.1	179.8	19.2	615	5.26	1203.8	1008.4	2.3	80	20.6	17.3	9.1	52	1.44
1419041	Rock	2.35	0.007	3.1	12.7	3.8	35	<0.1	7.4	5.5	384	1.80	5.4	1.2	15.1	43	<0.1	0.1	<0.1	21	0.83
1419042	Rock	2.49	<0.005	2.4	7.4	3.6	37	<0.1	2.3	3.8	422	1.97	1.8	2.3	13.4	35	<0.1	0.1	<0.1	16	0.65
1419043	Rock	2.51	0.006	2.3	4.6	3.6	40	<0.1	2.1	3.6	394	1.87	2.1	1.4	11.7	34	<0.1	0.2	<0.1	14	0.59
1419044	Rock	2.55	0.006	2.9	4.9	3.8	35	<0.1	1.7	3.3	407	1.92	2.7	6.1	14.3	32	<0.1	0.2	<0.1	13	0.72
1419045	Rock	2.60	0.009	2.9	10.5	3.5	43	<0.1	2.2	3.8	493	2.14	2.3	5.7	13.2	45	<0.1	0.2	<0.1	17	0.97
1419046	Rock	2.52	0.007	2.7	10.4	3.6	41	<0.1	2.0	3.5	449	2.12	2.2	<0.5	12.6	46	0.1	0.1	<0.1	12	0.71
1419047	Rock	2.52	<0.005	2.1	6.0	3.6	45	<0.1	2.1	4.4	506	2.14	1.8	3.7	11.4	36	<0.1	0.2	<0.1	13	0.81
1419048	Rock	2.43	<0.005	3.5	9.8	4.0	46	<0.1	2.3	3.8	506	2.27	2.8	5.0	13.4	47	<0.1	0.3	<0.1	14	0.75
1419049	Rock	2.82	0.006	2.0	15.6	3.1	39	<0.1	2.2	3.5	471	2.06	1.9	<0.5	11.8	38	<0.1	0.1	<0.1	11	0.67
1419050	Rock	1.05	<0.005	0.1	1.2	1.3	13	<0.1	0.7	0.9	218	0.41	<0.5	<0.5	0.2	51	<0.1	<0.1	<0.1	<2	20.03
1419051	Rock	2.79	0.006	2.8	10.7	3.0	38	<0.1	2.2	3.1	408	2.01	1.9	1.5	10.8	30	<0.1	0.2	<0.1	12	0.45
1419052	Rock	2.61	<0.005	4.2	13.9	2.8	38	<0.1	1.8	3.9	459	2.12	2.0	3.9	10.7	35	<0.1	0.1	<0.1	11	0.58
1419053	Rock	2.77	0.007	2.2	8.5	3.6	48	<0.1	2.8	4.9	571	2.20	1.9	3.1	12.9	79	<0.1	0.1	<0.1	19	1.24
1419054	Rock	3.00	<0.005	4.9	9.4	4.1	61	<0.1	4.3	5.1	734	2.38	1.8	2.2	10.3	188	<0.1	<0.1	<0.1	26	2.03
1419055	Rock	2.89	<0.005	2.4	13.4	4.4	34	<0.1	1.6	3.7	421	2.19	1.8	0.8	14.1	48	<0.1	0.1	<0.1	12	1.05
1419056	Rock	2.58	0.018	2.7	17.8	5.6	39	<0.1	1.8	4.0	478	2.37	4.7	<0.5	13.3	64	0.1	0.4	<0.1	12	1.03
1419057	Rock	2.60	0.010	2.6	12.8	7.6	39	<0.1	1.9	4.1	532	2.46	3.8	4.5	14.3	121	<0.1	0.4	<0.1	12	2.21
1419058	Rock	2.32	0.005	2.4	10.4	5.9	35	<0.1	2.1	4.0	498	2.43	2.1	59.7	14.1	85	<0.1	0.4	<0.1	11	1.71
1419059	Rock	2.94	<0.005	3.1	9.3	3.4	33	<0.1	2.0	3.4	394	2.06	1.6	3.2	13.7	47	<0.1	0.3	<0.1	12	0.77
1419060	Rock	1.96	<0.005	3.5	8.2	3.5	32	<0.1	2.0	3.4	401	2.08	1.4	1.7	13.4	46	0.1	0.2	<0.1	12	0.74



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419031	Rock	0.075	25	26	0.97	204	0.155	<20	1.19	0.078	0.79	2.6	<0.01	5.8	0.4	0.34	6	<0.5	<0.2
1419032	Rock	0.048	35	9	0.41	912	0.096	<20	0.86	0.078	0.53	2.8	<0.01	2.1	0.3	0.12	6	<0.5	<0.2
1419033	Rock	0.056	32	7	0.41	568	0.094	<20	0.82	0.073	0.46	4.1	0.01	1.7	0.3	0.29	5	0.6	<0.2
1419034	Rock	0.036	29	8	0.34	200	0.070	<20	0.66	0.064	0.38	4.0	<0.01	1.7	0.2	0.23	4	<0.5	<0.2
1419035	Rock	0.034	36	14	0.52	312	0.094	<20	0.72	0.089	0.50	2.5	<0.01	2.4	0.2	0.12	4	<0.5	<0.2
1419036	Rock	0.055	32	7	0.41	2161	0.086	<20	0.58	0.094	0.38	2.6	<0.01	2.4	0.2	0.23	5	<0.5	<0.2
1419037	Rock	0.045	34	10	0.41	269	0.080	<20	0.67	0.089	0.38	2.9	<0.01	2.5	0.2	0.23	5	0.5	<0.2
1419038	Rock	0.036	41	9	0.39	206	0.073	<20	0.83	0.067	0.44	2.8	<0.01	2.1	0.2	0.09	6	<0.5	<0.2
1419039	Rock	0.060	30	75	1.38	335	0.166	<20	1.51	0.053	1.22	1.4	0.01	6.1	0.5	0.07	7	<0.5	<0.2
1419040	Rock Pulp	0.064	10	41	0.85	252	0.078	<20	1.48	0.078	0.18	9.7	0.76	4.2	1.3	1.50	6	3.5	0.3
1419041	Rock	0.041	41	22	0.62	191	0.110	<20	0.99	0.068	0.67	2.6	<0.01	2.7	0.2	0.10	5	<0.5	<0.2
1419042	Rock	0.037	39	10	0.49	211	0.124	<20	1.00	0.080	0.67	3.1	<0.01	2.1	0.3	0.09	6	<0.5	<0.2
1419043	Rock	0.036	38	8	0.44	238	0.114	<20	0.90	0.064	0.60	3.3	<0.01	4.6	0.3	0.11	5	<0.5	<0.2
1419044	Rock	0.036	44	9	0.43	219	0.109	<20	0.92	0.070	0.60	3.4	<0.01	2.3	0.2	0.11	5	0.7	<0.2
1419045	Rock	0.044	37	10	0.51	244	0.123	<20	1.01	0.074	0.70	3.2	<0.01	2.0	0.3	0.19	6	<0.5	<0.2
1419046	Rock	0.040	39	8	0.44	219	0.114	<20	0.94	0.087	0.58	4.0	0.01	1.9	0.3	0.18	6	<0.5	<0.2
1419047	Rock	0.042	34	8	0.51	207	0.113	<20	1.05	0.059	0.70	2.4	<0.01	1.6	0.3	0.15	6	<0.5	<0.2
1419048	Rock	0.046	41	8	0.50	282	0.114	<20	1.07	0.076	0.68	2.7	<0.01	2.1	0.3	0.17	6	<0.5	<0.2
1419049	Rock	0.041	35	8	0.50	204	0.109	<20	0.98	0.064	0.63	3.1	<0.01	1.6	0.2	0.22	5	<0.5	<0.2
1419050	Rock	0.018	<1	<1	11.58	21	0.002	<20	0.04	<0.001	0.02	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
1419051	Rock	0.037	32	9	0.48	231	0.120	<20	0.97	0.065	0.70	3.0	<0.01	1.8	0.3	0.12	6	<0.5	<0.2
1419052	Rock	0.046	35	8	0.47	218	0.126	<20	1.00	0.070	0.67	4.1	<0.01	1.5	0.3	0.26	5	<0.5	<0.2
1419053	Rock	0.051	35	14	0.64	242	0.132	<20	1.10	0.068	0.73	2.7	<0.01	2.7	0.4	0.15	6	<0.5	<0.2
1419054	Rock	0.063	29	25	0.85	650	0.155	<20	1.29	0.054	0.93	2.6	<0.01	3.1	0.4	0.13	7	<0.5	<0.2
1419055	Rock	0.040	42	8	0.45	245	0.090	<20	0.96	0.074	0.57	2.7	<0.01	2.1	0.3	0.19	6	<0.5	<0.2
1419056	Rock	0.046	33	8	0.42	370	0.063	<20	0.91	0.056	0.51	2.5	0.04	2.8	0.2	0.24	5	<0.5	<0.2
1419057	Rock	0.049	26	11	0.42	1111	0.016	<20	0.64	0.043	0.33	1.5	0.02	4.1	0.2	0.26	4	<0.5	<0.2
1419058	Rock	0.044	32	10	0.41	649	0.025	<20	0.80	0.050	0.40	1.5	0.03	3.0	0.2	0.21	4	<0.5	<0.2
1419059	Rock	0.040	39	12	0.39	249	0.091	<20	0.84	0.062	0.51	3.2	<0.01	2.5	0.2	0.14	5	<0.5	<0.2
1419060	Rock	0.038	38	13	0.39	260	0.093	<20	0.87	0.071	0.52	3.6	<0.01	2.2	0.2	0.13	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419061	Rock	3.35	<0.005	3.8	29.0	3.0	37	<0.1	1.9	4.5	409	2.44	1.5	1.9	11.7	62	<0.1	<0.1	<0.1	13	0.92
1419062	Rock	3.23	<0.005	3.6	34.6	3.3	38	<0.1	2.5	5.3	414	2.67	3.3	0.8	13.0	58	<0.1	0.1	<0.1	13	0.59
1419063	Rock	2.77	<0.005	5.2	28.2	3.1	37	<0.1	1.7	5.6	451	2.70	7.9	1.3	12.9	37	<0.1	0.5	<0.1	17	0.61
1419064	Rock	2.94	<0.005	2.6	22.2	3.1	38	<0.1	2.4	5.0	485	2.61	4.4	<0.5	13.5	38	<0.1	0.2	<0.1	18	0.50
1419065	Rock	3.03	<0.005	3.1	15.2	3.5	42	<0.1	2.6	5.5	606	2.66	3.1	<0.5	13.8	53	<0.1	0.3	<0.1	17	1.25
1419066	Rock	3.19	<0.005	3.0	14.8	10.6	35	<0.1	1.5	3.9	773	2.08	3.0	<0.5	10.9	>2000	0.2	0.5	<0.1	20	6.13
1419067	Rock	1.01	0.008	4.3	13.5	6.8	37	<0.1	2.1	4.1	507	2.26	8.3	9.1	12.8	260	<0.1	0.8	<0.1	15	1.88
1419068	Rock	1.87	0.033	3.5	13.2	10.0	31	<0.1	2.4	3.2	486	2.01	12.9	31.6	11.6	399	<0.1	0.8	<0.1	12	2.88
1419069	Rock	1.60	0.055	4.0	12.4	11.5	36	0.1	2.0	3.0	458	1.75	16.7	24.7	11.3	442	<0.1	1.1	<0.1	10	3.05
1419070	Rock Pulp	0.12	0.889	5.0	32.8	5.0	42	0.3	24.0	9.5	405	2.54	7.0	361.9	0.9	39	0.1	0.8	0.1	59	0.85
1419071	Rock	0.99	0.030	3.7	14.2	17.7	66	<0.1	9.9	5.2	885	2.77	113.4	25.8	14.1	136	0.3	6.3	0.1	33	0.27
1419072	Rock	3.67	<0.005	4.4	4.9	7.0	50	<0.1	4.5	4.2	1114	2.04	111.0	11.6	14.9	62	0.1	2.4	<0.1	14	0.10
1419073	Rock	2.63	<0.005	1.6	5.0	5.6	43	<0.1	4.3	3.5	574	2.20	15.4	1.3	9.0	61	0.2	1.0	<0.1	17	0.10
1419074	Rock	2.56	<0.005	4.6	4.2	6.7	47	<0.1	2.5	3.5	1055	2.16	164.4	6.1	12.6	68	<0.1	1.4	0.1	26	0.09
1419075	Rock	2.40	0.023	5.4	3.6	10.7	47	<0.1	2.5	4.8	709	2.46	232.8	29.2	15.2	52	<0.1	1.9	<0.1	35	0.11
1419076	Rock	2.48	0.006	1.1	2.6	14.6	73	<0.1	1.9	3.6	688	2.68	40.1	4.6	17.4	66	0.1	1.8	<0.1	63	0.28
1419077	Rock	2.10	0.008	0.7	2.4	9.6	28	<0.1	1.6	1.8	552	1.47	87.6	<0.5	21.7	124	0.2	1.2	<0.1	18	1.07
1419078	Rock	2.70	0.010	1.3	3.4	28.2	51	<0.1	3.8	3.0	832	2.50	731.4	2.6	15.0	164	0.2	5.1	<0.1	36	0.58
1419079	Rock	2.93	0.014	0.8	2.7	7.2	51	<0.1	1.6	2.9	782	2.45	15.4	2.6	15.4	129	0.2	1.2	<0.1	57	2.61
1419080	Rock	0.75	0.010	<0.1	1.0	1.2	11	<0.1	<0.1	0.7	244	0.48	1.1	<0.5	<0.1	43	0.1	<0.1	<0.1	<2	20.73
1419081	Rock	2.81	0.031	0.8	2.3	12.0	69	<0.1	2.5	3.4	1048	2.88	20.7	23.3	11.4	179	0.4	1.4	<0.1	59	3.03
1419082	Rock	2.71	0.025	1.0	3.3	43.1	43	<0.1	4.4	2.4	1533	2.61	153.9	20.0	5.7	166	1.1	2.3	<0.1	33	0.35
1419083	Rock	2.41	0.020	1.6	8.3	34.0	79	<0.1	5.7	4.0	1184	3.44	141.7	23.0	8.3	139	0.5	3.4	<0.1	41	0.10
1419084	Rock	2.67	0.014	1.3	7.9	6.9	53	<0.1	5.8	4.3	995	2.77	23.0	10.0	11.9	194	0.2	3.3	<0.1	47	2.28
1419085	Rock	2.43	0.014	1.9	12.1	5.9	34	<0.1	2.0	3.0	717	1.93	8.1	7.2	12.6	102	0.1	3.5	<0.1	24	2.04
1419086	Rock	2.59	0.009	3.2	15.6	6.5	29	<0.1	2.3	4.1	590	2.13	5.6	1.5	14.2	116	<0.1	5.3	<0.1	8	1.05
1419087	Rock	2.49	<0.005	3.3	22.7	33.7	49	<0.1	1.8	4.1	512	2.36	14.4	<0.5	12.2	103	<0.1	6.7	<0.1	10	1.14
1419088	Rock	2.86	0.006	1.2	11.5	9.3	40	<0.1	2.2	3.3	639	1.99	6.5	<0.5	5.7	214	0.2	4.0	<0.1	20	2.22
1419089	Rock	2.34	0.006	0.7	5.6	7.2	37	<0.1	1.3	2.5	732	1.91	2.0	<0.5	4.8	274	<0.1	2.7	<0.1	24	2.20
1419090	Rock	1.77	0.007	0.9	6.3	7.1	35	<0.1	0.6	2.4	720	1.80	1.4	<0.5	4.7	269	<0.1	3.0	<0.1	24	2.15



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method Analyte Unit MDL		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419061	Rock	0.049	38	12	0.51	221	0.120	<20	0.95	0.081	0.61	4.9	0.02	1.8	0.3	0.51	5	<0.5	<0.2	
1419062	Rock	0.050	41	14	0.44	237	0.126	<20	1.02	0.096	0.62	6.1	0.03	1.4	0.2	0.50	6	<0.5	<0.2	
1419063	Rock	0.052	43	13	0.47	279	0.143	<20	1.20	0.084	0.74	3.9	0.01	1.9	0.3	0.30	6	<0.5	<0.2	
1419064	Rock	0.050	42	12	0.46	273	0.161	<20	1.18	0.082	0.77	4.3	0.02	1.7	0.3	0.30	6	<0.5	<0.2	
1419065	Rock	0.054	42	12	0.67	329	0.122	<20	1.30	0.060	0.79	2.3	0.03	2.2	0.4	0.25	6	<0.5	<0.2	
1419066	Rock	0.046	46	9	0.46	2073	0.070	<20	0.87	0.049	0.48	1.3	0.04	2.1	0.2	0.21	5	<0.5	<0.2	
1419067	Rock	0.044	41	13	0.43	486	0.077	<20	0.92	0.063	0.57	0.9	0.06	2.2	0.3	0.15	5	<0.5	<0.2	
1419068	Rock	0.043	37	17	0.35	411	0.050	<20	0.78	0.065	0.44	0.9	0.03	2.0	0.1	0.17	5	<0.5	<0.2	
1419069	Rock	0.040	36	15	0.30	494	0.039	<20	0.60	0.042	0.35	0.4	0.07	1.6	0.2	0.16	3	0.7	<0.2	
1419070	Rock Pulp	0.058	5	32	0.75	93	0.128	<20	1.54	0.085	0.13	10.8	0.05	4.9	0.1	<0.05	5	<0.5	0.2	
1419071	Rock	0.034	24	9	0.08	3859	0.007	<20	0.44	0.056	0.17	1.0	0.39	6.6	0.3	0.11	2	<0.5	0.2	
1419072	Rock	0.022	28	5	0.06	2307	0.004	<20	0.42	0.049	0.21	1.5	0.21	4.3	0.3	<0.05	2	<0.5	<0.2	
1419073	Rock	0.020	15	6	0.05	1967	0.002	<20	0.41	0.039	0.23	0.9	0.12	3.8	<0.1	<0.05	2	0.8	<0.2	
1419074	Rock	0.023	24	5	0.03	2734	0.001	<20	0.32	0.052	0.15	0.5	0.21	4.5	0.2	0.06	1	<0.5	<0.2	
1419075	Rock	0.037	31	4	0.03	1644	0.005	<20	0.32	0.076	0.13	0.5	0.25	5.3	0.2	<0.05	<1	<0.5	<0.2	
1419076	Rock	0.065	32	3	0.06	2491	0.024	<20	0.30	0.089	0.13	0.4	0.25	6.6	0.2	0.06	2	<0.5	<0.2	
1419077	Rock	0.012	24	4	0.03	3997	<0.001	<20	0.23	0.063	0.08	1.3	0.26	2.7	0.2	0.10	<1	<0.5	<0.2	
1419078	Rock	0.027	23	4	0.03	4140	<0.001	<20	0.29	0.063	0.10	1.7	0.80	4.6	0.6	0.11	<1	<0.5	0.2	
1419079	Rock	0.049	24	4	0.32	2634	0.006	<20	0.26	0.095	0.10	0.5	0.32	5.4	<0.1	0.10	<1	<0.5	<0.2	
1419080	Rock	0.016	<1	<1	11.72	36	<0.001	<20	<0.01	0.002	<0.01	<0.1	0.02	0.2	<0.1	<0.05	<1	<0.5	<0.2	
1419081	Rock	0.062	19	3	0.45	2237	0.001	<20	0.29	0.078	0.12	0.6	0.69	5.9	<0.1	0.22	1	<0.5	<0.2	
1419082	Rock	0.009	11	4	0.04	4421	<0.001	<20	0.37	0.029	0.18	1.3	1.85	5.2	0.8	0.12	<1	<0.5	<0.2	
1419083	Rock	0.015	24	4	0.05	3810	<0.001	<20	0.42	0.026	0.22	1.5	1.90	6.6	0.9	0.12	<1	<0.5	<0.2	
1419084	Rock	0.065	21	10	0.19	3749	0.007	<20	0.25	0.075	0.09	1.3	0.58	4.3	0.1	0.12	1	<0.5	<0.2	
1419085	Rock	0.036	22	4	0.07	1986	0.005	<20	0.28	0.054	0.13	0.9	0.34	4.2	<0.1	0.06	<1	<0.5	<0.2	
1419086	Rock	0.036	29	4	0.10	1587	0.003	<20	0.37	0.045	0.22	0.4	0.24	2.7	0.1	0.09	1	<0.5	<0.2	
1419087	Rock	0.025	20	4	0.10	850	0.001	<20	0.32	0.032	0.17	0.6	0.19	3.2	0.2	0.05	1	<0.5	<0.2	
1419088	Rock	0.036	9	4	0.23	1501	0.002	<20	0.35	0.037	0.22	0.4	0.13	4.0	0.1	0.06	2	<0.5	<0.2	
1419089	Rock	0.036	8	4	0.36	2021	0.002	<20	0.31	0.039	0.22	0.4	0.07	4.0	0.1	0.05	1	<0.5	<0.2	
1419090	Rock	0.033	8	4	0.35	1951	0.002	<20	0.29	0.037	0.21	0.4	0.06	3.8	0.2	<0.05	1	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419091	Rock	2.85	0.010	1.2	20.6	9.4	43	<0.1	2.6	3.9	512	2.07	14.9	4.8	10.1	139	<0.1	5.3	<0.1	21	1.61
1419092	Rock	2.92	0.011	1.2	94.3	23.0	106	0.1	18.4	8.2	1218	2.84	10.9	1.6	11.7	224	0.2	16.8	0.1	48	3.20
1419093	Rock	2.69	0.009	1.6	21.0	6.9	37	<0.1	1.6	3.3	503	1.93	5.6	<0.5	12.5	124	0.1	6.2	<0.1	11	1.31
1419094	Rock	2.70	<0.005	2.3	17.1	6.9	38	<0.1	2.5	4.4	508	2.36	3.8	<0.5	13.4	109	<0.1	6.1	<0.1	10	1.12
1419095	Rock	2.91	0.007	2.0	11.2	8.9	30	<0.1	1.8	2.8	494	1.63	3.8	3.1	10.1	158	<0.1	3.7	0.1	10	2.05
1419096	Rock	2.86	<0.005	2.9	5.9	4.9	27	<0.1	3.4	3.2	440	1.72	2.8	3.6	10.6	158	<0.1	2.0	0.1	9	1.46
1419097	Rock	2.53	0.008	3.2	5.5	6.1	27	<0.1	3.8	3.4	387	1.79	3.9	4.2	11.3	108	<0.1	2.2	0.3	8	1.00
1419098	Rock	2.85	0.005	1.9	16.2	17.4	41	<0.1	2.5	5.1	522	2.82	13.5	6.5	10.0	116	<0.1	5.1	0.2	9	1.14
1419099	Rock	2.90	0.006	2.1	13.1	7.5	41	<0.1	1.8	3.5	352	2.27	6.1	3.7	11.1	110	0.2	3.8	0.1	8	0.81
1419100	Rock Pulp	0.13	2.211	56.5	2287.5	1376.1	3987	28.1	190.0	19.9	639	5.19	1198.3	1318.6	2.4	77	20.6	16.5	9.7	54	1.51
1419101	Rock	2.66	<0.005	2.0	7.2	8.3	40	<0.1	2.2	4.2	486	2.44	7.2	2.0	9.4	110	<0.1	2.1	<0.1	8	1.47
1419102	Rock	2.70	0.006	1.6	11.5	6.4	42	<0.1	2.2	4.1	556	2.49	4.1	0.6	14.2	116	<0.1	4.7	0.1	8	1.10
1419103	Rock	3.01	0.055	2.1	15.0	5.1	39	<0.1	1.6	3.5	566	2.33	2.9	0.8	12.8	126	<0.1	5.1	<0.1	6	1.32
1419104	Rock	2.41	0.007	1.7	4.7	4.6	31	<0.1	2.2	2.7	472	1.79	2.2	1.7	9.4	148	<0.1	1.6	<0.1	6	1.65
1419105	Rock	2.76	<0.005	2.0	11.8	5.7	48	<0.1	1.4	4.0	698	2.55	3.8	1.5	11.7	255	<0.1	3.7	0.1	9	2.31
1419106	Rock	2.89	<0.005	2.2	26.9	8.0	49	<0.1	1.7	4.0	574	2.68	9.5	<0.5	11.5	170	<0.1	8.3	<0.1	6	1.25
1419107	Rock	2.82	0.006	1.2	25.2	16.6	20	<0.1	1.4	3.2	601	1.82	20.9	7.8	4.5	289	<0.1	4.4	<0.1	6	1.18
1419108	Rock	2.75	0.005	3.2	9.5	10.8	19	<0.1	1.6	2.1	493	1.58	14.0	4.0	7.5	149	<0.1	2.0	0.4	3	1.51
1419109	Rock	3.04	<0.005	7.7	6.2	5.9	22	<0.1	1.7	2.9	412	1.83	9.0	2.6	9.7	144	<0.1	1.2	0.3	3	1.31
1419110	Rock Pulp	0.12	0.874	4.2	35.3	5.1	49	0.2	24.5	9.9	403	2.58	6.0	448.9	0.8	38	<0.1	0.9	<0.1	59	0.84
1419111	Rock	2.95	0.013	28.1	5.4	13.8	26	<0.1	2.0	2.6	696	2.48	28.3	2.9	11.2	165	<0.1	2.3	<0.1	23	2.20
1419112	Rock	3.07	0.019	1.6	8.5	10.0	30	<0.1	1.5	2.7	874	2.00	4.5	14.9	10.9	243	<0.1	2.3	<0.1	26	3.30
1419113	Rock	2.88	<0.005	2.0	4.6	6.3	40	<0.1	2.1	2.8	533	2.14	5.3	4.0	12.0	152	<0.1	1.4	0.1	16	1.88
1419114	Rock	3.14	0.009	2.5	6.1	8.3	34	<0.1	1.9	4.0	560	2.48	12.2	11.7	13.7	224	0.1	1.5	0.3	6	2.03
1419115	Rock	2.84	<0.005	1.4	14.3	8.1	43	<0.1	2.5	4.3	477	2.16	9.5	10.6	13.4	158	0.1	2.4	0.3	13	1.73
1419116	Rock	3.04	0.016	0.9	5.5	9.5	44	<0.1	2.8	4.6	580	2.47	13.4	5.6	12.9	146	<0.1	1.2	<0.1	10	2.09
1419117	Rock	2.91	<0.005	1.1	7.2	32.7	34	<0.1	2.9	5.7	559	2.28	15.9	4.0	8.1	205	<0.1	1.7	<0.1	9	1.77
1419118	Rock	2.93	0.008	1.3	10.8	7.1	50	<0.1	8.9	7.1	780	2.76	2.9	<0.5	11.5	355	<0.1	1.5	<0.1	14	3.38
1419119	Rock	2.96	<0.005	1.5	4.5	5.1	26	<0.1	2.7	3.3	456	1.92	2.9	4.1	16.0	271	<0.1	1.5	<0.1	6	2.24
1419120	Rock	0.63	<0.005	0.2	1.9	1.3	11	<0.1	1.4	0.8	246	0.52	<0.5	3.6	0.2	45	<0.1	<0.1	<0.1	<2	21.37



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419091	Rock	0.034	14	4	0.21	1837	0.001	<20	0.33	0.048	0.19	0.3	0.29	3.7	0.2	0.11	1	<0.5	<0.2
1419092	Rock	0.076	14	14	0.60	2366	0.005	<20	0.43	0.034	0.29	0.2	1.83	10.0	0.4	0.08	2	<0.5	<0.2
1419093	Rock	0.033	24	5	0.25	1330	0.003	<20	0.34	0.039	0.22	0.5	0.35	3.7	0.1	0.08	1	<0.5	<0.2
1419094	Rock	0.042	29	5	0.20	887	0.007	<20	0.41	0.031	0.27	0.5	0.30	4.2	<0.1	0.14	2	<0.5	<0.2
1419095	Rock	0.022	15	5	0.44	1755	<0.001	<20	0.27	0.027	0.17	1.2	0.30	2.6	<0.1	0.11	<1	<0.5	<0.2
1419096	Rock	0.026	19	6	0.27	1320	0.005	<20	0.35	0.029	0.24	0.3	0.14	3.1	0.1	0.05	2	<0.5	<0.2
1419097	Rock	0.022	15	7	0.20	829	0.003	<20	0.36	0.033	0.23	0.4	0.11	3.5	0.2	<0.05	2	<0.5	<0.2
1419098	Rock	0.032	11	5	0.13	878	0.001	<20	0.36	0.021	0.23	0.6	0.36	3.0	0.1	0.12	1	<0.5	<0.2
1419099	Rock	0.027	16	5	0.10	1629	0.005	<20	0.41	0.035	0.26	0.3	0.31	3.2	0.2	0.07	2	<0.5	<0.2
1419100	Rock Pulp	0.066	11	45	0.87	219	0.080	<20	1.51	0.074	0.19	8.1	0.74	4.6	1.4	1.53	6	4.9	0.7
1419101	Rock	0.029	11	5	0.17	633	0.002	<20	0.37	0.022	0.24	0.4	0.22	3.0	0.1	<0.05	1	0.6	<0.2
1419102	Rock	0.048	26	5	0.17	397	0.014	<20	0.52	0.032	0.35	0.5	0.20	3.8	0.2	<0.05	2	<0.5	<0.2
1419103	Rock	0.046	24	5	0.19	558	0.011	<20	0.49	0.024	0.34	0.4	0.11	3.0	0.3	0.07	3	<0.5	<0.2
1419104	Rock	0.029	15	6	0.21	877	0.005	<20	0.28	0.032	0.18	1.1	0.10	2.8	0.1	0.09	1	<0.5	<0.2
1419105	Rock	0.050	24	6	0.33	2023	0.005	<20	0.39	0.037	0.26	0.5	0.11	3.4	0.2	0.11	2	<0.5	<0.2
1419106	Rock	0.039	15	5	0.33	1151	0.004	<20	0.44	0.034	0.28	0.3	0.22	3.7	0.2	0.22	2	0.6	<0.2
1419107	Rock	0.006	5	5	0.31	3659	<0.001	<20	0.36	0.010	0.22	3.8	0.68	2.3	0.2	0.14	<1	<0.5	<0.2
1419108	Rock	0.014	7	5	0.37	1829	<0.001	<20	0.41	0.005	0.30	0.6	0.40	1.8	0.2	0.07	1	<0.5	0.2
1419109	Rock	0.027	10	5	0.28	418	<0.001	<20	0.38	0.019	0.25	0.4	0.33	2.8	0.1	0.06	1	<0.5	<0.2
1419110	Rock Pulp	0.055	4	33	0.76	97	0.124	<20	1.54	0.084	0.13	10.6	0.03	5.1	<0.1	<0.05	5	<0.5	<0.2
1419111	Rock	0.059	17	6	0.43	1175	<0.001	<20	0.35	0.037	0.21	1.4	1.34	3.6	0.2	0.16	1	<0.5	<0.2
1419112	Rock	0.034	12	7	0.57	1780	0.002	<20	0.26	0.042	0.15	0.7	0.70	4.6	0.1	0.17	<1	0.5	<0.2
1419113	Rock	0.048	17	6	0.30	976	0.003	<20	0.34	0.053	0.22	0.4	0.16	3.7	0.1	0.11	1	0.6	<0.2
1419114	Rock	0.053	19	6	0.25	1765	0.002	<20	0.40	0.029	0.26	0.3	0.18	3.5	0.1	0.13	2	<0.5	<0.2
1419115	Rock	0.047	19	5	0.31	481	0.002	<20	0.41	0.037	0.26	0.3	0.24	3.6	0.1	0.12	2	<0.5	<0.2
1419116	Rock	0.050	19	6	0.43	420	0.002	<20	0.44	0.027	0.26	0.3	0.14	3.9	0.2	0.09	2	<0.5	<0.2
1419117	Rock	0.027	8	5	0.36	1563	0.002	<20	0.43	0.027	0.27	0.5	0.42	3.4	0.2	0.25	2	<0.5	<0.2
1419118	Rock	0.062	17	14	0.71	1265	0.019	<20	0.65	0.027	0.46	0.3	0.19	5.0	0.3	0.16	3	<0.5	<0.2
1419119	Rock	0.036	18	8	0.39	1726	0.020	<20	0.52	0.043	0.35	0.7	0.14	1.8	0.2	0.15	3	<0.5	<0.2
1419120	Rock	0.017	<1	<1	12.21	36	<0.001	<20	0.03	0.002	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419121	Rock	3.13	0.006	0.7	2.9	3.8	19	<0.1	1.4	2.6	394	1.69	2.7	3.7	18.9	182	<0.1	1.2	<0.1	4	1.75
1419122	Rock	2.86	0.009	1.7	3.9	4.0	21	<0.1	2.0	2.8	351	1.84	1.6	1.4	15.2	265	<0.1	2.8	0.1	7	1.36
1419123	Rock	2.66	<0.005	5.1	4.4	5.6	25	<0.1	2.2	2.9	523	1.82	2.7	5.6	16.4	375	<0.1	2.4	0.3	9	2.46
1419124	Rock	3.16	<0.005	2.3	5.8	6.6	35	<0.1	1.5	3.3	467	2.21	2.6	1.7	14.4	234	<0.1	2.1	0.2	9	1.43
1419125	Rock	2.79	<0.005	3.6	3.7	7.1	36	<0.1	1.9	3.1	509	2.13	2.7	<0.5	17.2	215	<0.1	2.3	0.3	6	1.46
1419126	Rock	3.13	<0.005	2.5	12.3	6.2	29	<0.1	2.0	4.0	455	2.22	7.0	2.1	14.5	202	0.1	3.9	0.2	7	1.26
1419127	Rock	2.89	<0.005	1.6	7.3	16.0	48	<0.1	1.9	3.6	794	2.56	36.9	2.4	7.0	278	0.4	3.1	<0.1	23	2.91
1419128	Rock	3.12	<0.005	2.4	20.2	9.1	80	<0.1	1.8	3.4	888	2.84	41.7	5.7	11.2	148	0.2	2.3	<0.1	26	2.31
1419129	Rock	3.28	0.012	2.4	5.0	5.9	43	<0.1	1.5	4.5	769	2.73	22.3	2.1	12.6	127	<0.1	2.1	<0.1	20	1.95
1419130	Rock	2.09	<0.005	1.5	5.6	6.2	45	<0.1	2.2	3.9	768	2.66	20.6	12.4	12.5	134	<0.1	1.6	<0.1	21	1.88
1419131	Rock	2.18	0.007	3.5	6.4	43.2	42	<0.1	1.7	2.9	1547	3.96	171.4	3.8	8.3	244	0.8	6.7	<0.1	59	1.77
1419132	Rock	3.06	<0.005	1.9	4.9	18.1	44	<0.1	2.5	3.6	916	2.80	50.1	<0.5	8.2	213	0.3	2.2	<0.1	32	1.85
1419133	Rock	3.03	0.010	2.3	3.5	46.5	54	<0.1	1.8	2.9	1233	3.77	719.9	9.2	7.4	227	0.7	8.3	<0.1	46	1.29
1419134	Rock	2.78	0.023	2.8	6.5	45.0	35	<0.1	1.8	4.1	1049	2.95	4479.8	25.6	9.6	157	0.6	10.8	<0.1	27	0.95
1419135	Rock	3.00	0.006	1.7	2.8	21.4	27	<0.1	2.0	1.7	901	2.09	528.9	6.3	9.3	195	0.3	5.5	<0.1	22	1.42
1419136	Rock	2.87	0.006	1.8	4.2	34.4	30	<0.1	4.6	2.5	1224	2.45	860.0	3.7	10.5	241	0.3	8.3	<0.1	35	2.65
1419137	Rock	3.02	<0.005	2.4	7.8	9.8	86	<0.1	30.1	13.7	1035	4.18	44.4	<0.5	10.1	290	0.2	2.3	<0.1	62	2.73
1419138	Rock	3.02	<0.005	2.1	19.4	14.8	62	<0.1	28.8	12.4	1023	3.23	59.7	2.7	9.6	274	0.3	6.0	<0.1	58	3.31



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000258.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1419121	Rock	0.027	33	6	0.32	982	0.024	<20	0.51	0.035	0.34	0.7	0.03	1.2	0.2	0.09	3	<0.5	<0.2	
1419122	Rock	0.042	32	7	0.44	2637	0.052	<20	0.72	0.043	0.53	0.6	0.05	2.0	0.2	0.13	4	<0.5	<0.2	
1419123	Rock	0.058	43	7	0.52	2502	0.045	<20	0.74	0.039	0.54	0.7	0.10	2.6	0.3	0.11	4	<0.5	<0.2	
1419124	Rock	0.039	32	9	0.43	1330	0.059	<20	0.74	0.045	0.54	0.8	0.19	2.6	0.4	0.16	4	<0.5	<0.2	
1419125	Rock	0.030	30	9	0.41	875	0.043	<20	0.70	0.045	0.51	0.8	0.11	2.5	0.4	0.14	4	<0.5	<0.2	
1419126	Rock	0.039	23	7	0.32	702	0.027	<20	0.59	0.031	0.41	0.8	0.27	2.6	0.3	0.15	3	<0.5	<0.2	
1419127	Rock	0.043	12	6	0.65	1227	0.007	<20	0.54	0.019	0.37	0.7	0.57	3.6	0.3	0.20	3	<0.5	<0.2	
1419128	Rock	0.048	20	8	0.65	1003	0.013	<20	0.42	0.047	0.28	2.0	0.92	4.8	0.3	0.27	2	1.1	<0.2	
1419129	Rock	0.044	22	8	0.62	697	0.042	<20	0.60	0.047	0.42	2.0	0.47	3.7	0.3	0.20	3	<0.5	<0.2	
1419130	Rock	0.045	21	8	0.61	727	0.039	<20	0.54	0.042	0.39	1.8	0.46	3.6	0.2	0.20	3	<0.5	<0.2	
1419131	Rock	0.026	11	15	0.62	620	0.002	<20	0.23	0.052	0.11	5.6	2.58	7.7	1.2	0.36	<1	0.6	<0.2	
1419132	Rock	0.043	11	10	0.58	2018	0.001	<20	0.27	0.042	0.16	1.8	0.68	5.5	0.3	0.22	1	<0.5	<0.2	
1419133	Rock	0.043	12	9	0.49	530	<0.001	<20	0.29	0.047	0.15	5.6	2.99	5.7	1.7	0.36	<1	<0.5	<0.2	
1419134	Rock	0.027	7	8	0.36	655	<0.001	<20	0.32	0.009	0.20	4.4	3.79	4.1	2.8	0.46	<1	<0.5	<0.2	
1419135	Rock	0.026	11	7	0.43	2138	<0.001	<20	0.30	0.031	0.15	2.5	1.09	4.4	0.8	0.21	<1	<0.5	<0.2	
1419136	Rock	0.041	14	12	0.77	2121	0.001	<20	0.20	0.054	0.09	2.5	1.31	5.8	0.8	0.23	<1	<0.5	<0.2	
1419137	Rock	0.096	28	81	1.53	2118	0.208	<20	1.90	0.042	1.70	0.7	0.33	8.0	0.9	0.12	8	<0.5	<0.2	
1419138	Rock	0.077	25	72	1.44	1807	0.111	<20	1.24	0.050	1.11	0.8	1.21	9.4	0.5	0.12	5	<0.5	<0.2	



QUALITY CONTROL REPORT

WHI16000258.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1419009	Rock	2.33	0.031	2.5	5.6	14.0	43	0.1	5.9	6.2	975	2.08	21.2	35.5	12.5	85	<0.1	2.1	0.2	16	1.15
REP 1419009	QC			2.5	5.5	13.6	44	0.2	6.0	6.0	951	2.05	21.0	25.6	13.0	84	<0.1	2.1	0.2	15	1.14
1419042	Rock	2.49	<0.005	2.4	7.4	3.6	37	<0.1	2.3	3.8	422	1.97	1.8	2.3	13.4	35	<0.1	0.1	<0.1	16	0.65
REP 1419042	QC			2.8	7.5	3.6	39	<0.1	2.4	3.6	418	1.95	1.7	5.1	13.3	35	<0.1	0.1	<0.1	16	0.64
1419061	Rock	3.35	<0.005	3.8	29.0	3.0	37	<0.1	1.9	4.5	409	2.44	1.5	1.9	11.7	62	<0.1	<0.1	<0.1	13	0.92
REP 1419061	QC		<0.005																		
1419072	Rock	3.67	<0.005	4.4	4.9	7.0	50	<0.1	4.5	4.2	1114	2.04	111.0	11.6	14.9	62	0.1	2.4	<0.1	14	0.10
REP 1419072	QC		0.008																		
1419077	Rock	2.10	0.008	0.7	2.4	9.6	28	<0.1	1.6	1.8	552	1.47	87.6	<0.5	21.7	124	0.2	1.2	<0.1	18	1.07
REP 1419077	QC			0.9	2.8	9.7	28	<0.1	2.0	1.9	551	1.48	90.1	<0.5	20.9	124	0.4	1.5	<0.1	17	1.07
1419112	Rock	3.07	0.019	1.6	8.5	10.0	30	<0.1	1.5	2.7	874	2.00	4.5	14.9	10.9	243	<0.1	2.3	<0.1	26	3.30
REP 1419112	QC			1.5	8.2	10.1	29	<0.1	1.1	2.9	859	1.97	4.1	10.1	10.5	243	<0.1	2.5	<0.1	25	3.25
1419134	Rock	2.78	0.023	2.8	6.5	45.0	35	<0.1	1.8	4.1	1049	2.95	4479.8	25.6	9.6	157	0.6	10.8	<0.1	27	0.95
REP 1419134	QC		0.024																		
1419138	Rock	3.02	<0.005	2.1	19.4	14.8	62	<0.1	28.8	12.4	1023	3.23	59.7	2.7	9.6	274	0.3	6.0	<0.1	58	3.31
REP 1419138	QC		<0.005	2.5	18.1	15.3	61	<0.1	28.0	12.1	1039	3.29	59.3	1.3	10.1	273	0.2	5.8	<0.1	59	3.36
Core Reject Duplicates																					
1419023	Rock	2.41	0.009	5.2	55.2	10.1	40	0.1	3.2	5.6	438	2.87	68.1	11.9	16.5	36	<0.1	2.2	0.3	16	0.20
DUP 1419023	QC		0.007	5.5	56.2	9.9	40	0.1	3.7	5.8	436	2.82	66.5	6.8	16.3	35	<0.1	2.3	0.4	16	0.20
1419057	Rock	2.60	0.010	2.6	12.8	7.6	39	<0.1	1.9	4.1	532	2.46	3.8	4.5	14.3	121	<0.1	0.4	<0.1	12	2.21
DUP 1419057	QC		0.008	2.9	11.8	7.7	35	<0.1	2.2	4.2	538	2.53	4.0	5.0	13.8	121	0.1	0.5	<0.1	12	2.24
1419091	Rock	2.85	0.010	1.2	20.6	9.4	43	<0.1	2.6	3.9	512	2.07	14.9	4.8	10.1	139	<0.1	5.3	<0.1	21	1.61
DUP 1419091	QC		0.007	1.8	20.7	9.3	43	<0.1	2.8	4.0	513	2.06	14.1	5.9	9.5	141	<0.1	6.4	<0.1	21	1.63
1419125	Rock	2.79	<0.005	3.6	3.7	7.1	36	<0.1	1.9	3.1	509	2.13	2.7	<0.5	17.2	215	<0.1	2.3	0.3	6	1.46
DUP 1419125	QC		<0.005	2.2	5.8	6.8	36	<0.1	1.5	2.7	503	2.09	2.8	1.0	17.7	212	<0.1	2.5	0.3	6	1.46
Reference Materials																					
STD DS10	Standard			13.2	145.2	137.9	370	1.8	73.2	12.1	875	2.74	46.6	127.0	7.1	70	2.7	9.5	11.7	42	1.05
STD DS10	Standard			13.4	140.7	139.5	354	1.7	69.1	12.0	858	2.62	45.5	61.7	6.7	66	2.6	8.6	11.1	39	1.03



QUALITY CONTROL REPORT

WHI16000258.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1419009	Rock	0.036	17	10	0.09	1085	0.004	<20	0.54	0.040	0.31	0.3	0.28	5.6	0.3	<0.05	2	<0.5	<0.2
REP 1419009	QC	0.037	16	9	0.09	1063	0.003	<20	0.52	0.038	0.30	0.3	0.21	5.9	0.3	<0.05	2	<0.5	<0.2
1419042	Rock	0.037	39	10	0.49	211	0.124	<20	1.00	0.080	0.67	3.1	<0.01	2.1	0.3	0.09	6	<0.5	<0.2
REP 1419042	QC	0.037	39	9	0.49	208	0.122	<20	0.99	0.078	0.66	3.4	<0.01	2.1	0.3	0.09	6	<0.5	<0.2
1419061	Rock	0.049	38	12	0.51	221	0.120	<20	0.95	0.081	0.61	4.9	0.02	1.8	0.3	0.51	5	<0.5	<0.2
REP 1419061	QC																		
1419072	Rock	0.022	28	5	0.06	2307	0.004	<20	0.42	0.049	0.21	1.5	0.21	4.3	0.3	<0.05	2	<0.5	<0.2
REP 1419072	QC																		
1419077	Rock	0.012	24	4	0.03	3997	<0.001	<20	0.23	0.063	0.08	1.3	0.26	2.7	0.2	0.10	<1	<0.5	<0.2
REP 1419077	QC	0.012	22	4	0.03	3874	<0.001	<20	0.22	0.061	0.08	1.3	0.31	3.0	0.2	0.10	<1	<0.5	<0.2
1419112	Rock	0.034	12	7	0.57	1780	0.002	<20	0.26	0.042	0.15	0.7	0.70	4.6	0.1	0.17	<1	0.5	<0.2
REP 1419112	QC	0.034	11	6	0.56	1760	0.002	<20	0.25	0.041	0.15	0.7	0.60	5.2	0.1	0.17	<1	<0.5	<0.2
1419134	Rock	0.027	7	8	0.36	655	<0.001	<20	0.32	0.009	0.20	4.4	3.79	4.1	2.8	0.46	<1	<0.5	<0.2
REP 1419134	QC																		
1419138	Rock	0.077	25	72	1.44	1807	0.111	<20	1.24	0.050	1.11	0.8	1.21	9.4	0.5	0.12	5	<0.5	<0.2
REP 1419138	QC	0.081	26	73	1.47	1833	0.115	<20	1.26	0.051	1.14	0.8	1.24	9.8	0.6	0.13	5	<0.5	<0.2
Core Reject Duplicates																			
1419023	Rock	0.050	43	7	0.28	326	0.023	<20	0.90	0.071	0.27	0.5	0.03	3.3	0.1	<0.05	5	0.6	<0.2
DUP 1419023	QC	0.046	43	7	0.28	328	0.023	<20	0.89	0.070	0.27	0.4	0.04	3.5	0.2	<0.05	5	1.0	<0.2
1419057	Rock	0.049	26	11	0.42	1111	0.016	<20	0.64	0.043	0.33	1.5	0.02	4.1	0.2	0.26	4	<0.5	<0.2
DUP 1419057	QC	0.051	26	12	0.42	1132	0.016	<20	0.67	0.048	0.34	1.6	0.02	4.1	0.1	0.27	4	<0.5	<0.2
1419091	Rock	0.034	14	4	0.21	1837	0.001	<20	0.33	0.048	0.19	0.3	0.29	3.7	0.2	0.11	1	<0.5	<0.2
DUP 1419091	QC	0.033	13	5	0.21	1798	0.001	<20	0.32	0.046	0.18	0.4	0.21	3.7	0.2	0.11	1	<0.5	<0.2
1419125	Rock	0.030	30	9	0.41	875	0.043	<20	0.70	0.045	0.51	0.8	0.11	2.5	0.4	0.14	4	<0.5	<0.2
DUP 1419125	QC	0.030	30	8	0.41	859	0.044	<20	0.68	0.041	0.50	0.9	0.18	2.2	0.3	0.14	4	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.076	17	52	0.80	430	0.075	<20	1.03	0.071	0.34	2.9	0.28	2.9	5.5	0.28	4	2.9	4.7
STD DS10	Standard	0.075	16	50	0.76	400	0.072	<20	1.00	0.066	0.32	3.0	0.30	2.9	5.0	0.28	4	3.5	4.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000258.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD DS10	Standard			13.9	157.6	149.4	355	1.5	75.5	13.2	899	2.74	41.8	192.0	7.1	64	2.3	8.2	11.1	42	1.07	
STD DS10	Standard			13.0	149.1	145.9	357	1.5	70.3	12.8	855	2.72	44.1	64.1	6.8	64	1.9	7.7	11.1	41	1.06	
STD DS10	Standard			12.8	146.9	143.8	369	2.2	71.9	12.0	865	2.70	44.9	82.5	6.8	64	2.4	8.3	13.6	41	1.02	
STD OREAS45EA	Standard			1.5	719.3	13.2	30	0.3	394.8	49.4	410	21.84	12.2	61.5	9.5	4	<0.1	0.4	0.2	311	0.04	
STD OREAS45EA	Standard			1.4	684.1	13.1	31	0.2	397.3	48.4	400	22.10	10.8	49.0	9.4	4	0.1	0.3	0.2	306	0.04	
STD OREAS45EA	Standard			1.7	745.2	14.3	35	0.2	429.0	57.2	449	23.18	12.2	51.8	10.9	4	<0.1	0.3	0.2	354	0.04	
STD OREAS45EA	Standard			1.5	700.6	13.9	33	0.2	394.6	52.0	426	22.29	10.8	50.3	10.5	4	<0.1	0.3	0.3	327	0.04	
STD OREAS45EA	Standard			1.6	672.9	12.7	30	0.2	378.7	50.2	396	20.98	11.2	53.0	9.3	4	<0.1	0.4	0.3	298	0.03	
STD OXD108	Standard		0.413																			
STD OXD108	Standard		0.401																			
STD OXD108	Standard		0.399																			
STD OXI121	Standard		1.840																			
STD OXI121	Standard		1.765																			
STD OXI121	Standard		1.772																			
STD OXN117	Standard		7.656																			
STD OXN117	Standard		7.544																			
STD OXN117	Standard		7.142																			
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
STD OXD108 Expected			0.414																			
STD OXN117 Expected			7.679																			
STD OXI121 Expected			1.834																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	0.6	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			



QUALITY CONTROL REPORT

WHI16000258.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.075	17	54	0.78	409	0.075	<20	1.03	0.069	0.34	3.0	0.25	3.0	5.2	0.28	4	1.3	4.3
STD DS10	Standard	0.068	17	56	0.76	401	0.075	<20	0.99	0.065	0.33	3.1	0.29	2.8	5.6	0.27	4	3.2	6.0
STD DS10	Standard	0.072	16	50	0.76	419	0.066	<20	0.98	0.066	0.32	3.2	0.32	2.9	4.9	0.29	4	3.5	5.0
STD OREAS45EA	Standard	0.032	7	822	0.08	145	0.092	<20	3.29	0.022	0.06	<0.1	<0.01	80.4	<0.1	<0.05	12	2.0	<0.2
STD OREAS45EA	Standard	0.029	7	823	0.08	139	0.091	<20	3.30	0.022	0.05	<0.1	<0.01	78.2	<0.1	<0.05	12	1.6	<0.2
STD OREAS45EA	Standard	0.032	8	950	0.11	149	0.103	<20	3.47	0.018	0.05	<0.1	0.02	87.1	<0.1	<0.05	13	1.3	0.4
STD OREAS45EA	Standard	0.028	7	891	0.11	144	0.098	<20	3.26	0.017	0.05	<0.1	0.01	84.1	<0.1	<0.05	12	<0.5	<0.2
STD OREAS45EA	Standard	0.031	6	827	0.11	138	0.090	<20	3.20	0.021	0.06	<0.1	0.02	84.1	<0.1	<0.05	13	1.3	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.02	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	0.7	<0.2
BLK	Blank																		
BLK	Blank																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000258.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank	<0.005																			
BLK	Blank	0.006																			
BLK	Blank	<0.005																			
BLK	Blank	0.020																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.7	4.7	1.6	33	<0.1	1.0	3.5	417	1.75	1.3	<0.5	2.4	36	0.1	<0.1	<0.1	23	0.72	
ROCK-WHI	Prep Blank	<0.005	0.7	3.6	1.6	31	<0.1	1.0	3.6	429	1.79	0.7	<0.5	2.5	31	0.1	<0.1	<0.1	23	0.65	



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000258.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.041	6	3	0.39	91	0.089	26	1.06	0.152	0.14	0.1	<0.01	4.4	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.041	6	3	0.40	86	0.086	40	1.07	0.163	0.14	0.1	<0.01	3.9	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 06, 2016
Report Date: September 21, 2016
Page: 1 of 5

CERTIFICATE OF ANALYSIS

WHI16000259.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-02-Rock
P.O. Number
Number of Samples: 95

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	91	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	95	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	95	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	95	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419139	Rock	2.81	<0.005	2.1	3.2	19.0	42	<0.1	2.6	2.9	687	2.01	188.6	3.1	13.5	201	0.1	1.6	<0.1	21	2.16
1419140	Rock Pulp	0.12	2.405	59.8	2183.4	1306.2	3715	27.0	183.5	18.6	631	5.25	1164.9	4015.0	2.3	80	21.0	17.1	11.4	56	1.47
1419141	Rock	2.97	0.064	2.0	3.3	15.4	34	<0.1	1.6	3.2	720	2.02	73.3	50.2	13.6	238	0.3	1.3	<0.1	10	2.68
1419142	Rock	2.89	0.006	2.6	3.0	6.3	19	<0.1	1.5	2.2	472	1.56	18.3	1.9	18.1	110	<0.1	1.5	<0.1	5	1.43
1419143	Rock	2.66	<0.005	2.4	4.0	5.9	23	<0.1	2.1	3.4	594	1.94	23.7	2.0	16.8	147	<0.1	1.9	<0.1	7	1.66
1419144	Rock	0.94	0.228	2.9	14.1	16.5	73	0.3	9.7	6.8	758	2.92	8.2	174.5	8.0	85	0.2	1.7	0.4	36	1.12
1419145	Rock	2.39	0.246	2.2	5.8	10.3	50	0.1	7.5	6.0	548	2.64	9.2	91.4	3.0	126	0.4	1.7	0.4	33	3.16
1419146	Rock	2.95	0.025	3.7	5.6	7.3	15	<0.1	16.5	1.6	241	1.27	5.2	22.2	0.7	46	<0.1	0.9	<0.1	10	0.39
1419147	Rock	4.77	0.162	2.9	8.2	11.1	76	0.1	10.4	7.6	704	3.02	6.3	223.8	4.3	107	0.4	1.6	0.3	48	2.57
1419148	Rock	2.99	0.042	3.5	22.6	9.1	78	<0.1	14.5	10.3	716	3.32	2.4	37.4	8.1	70	0.2	2.2	0.8	67	0.94
1419149	Rock	2.85	0.006	1.3	9.9	4.9	88	<0.1	11.8	9.8	495	3.01	3.0	2.6	9.4	57	0.2	0.9	0.6	73	0.31
1419150	Rock	0.56	<0.005	0.2	8.7	1.3	16	<0.1	0.5	0.8	224	0.43	0.6	<0.5	<0.1	48	0.1	<0.1	<0.1	6	18.58
1419151	Rock	3.60	<0.005	0.9	4.1	6.6	20	<0.1	1.5	1.5	317	1.13	4.7	2.6	16.0	28	0.1	0.7	<0.1	14	0.09
1419152	Rock	3.33	<0.005	1.0	5.2	7.3	16	<0.1	1.6	1.1	356	1.05	6.6	1.5	21.1	47	<0.1	0.8	0.1	11	0.06
1419153	Rock	3.30	0.042	1.9	4.3	18.8	27	0.1	2.7	2.8	475	1.47	6.1	38.3	17.3	39	0.4	0.8	<0.1	19	0.07
1419154	Rock	2.80	0.160	3.3	5.5	45.7	37	0.5	2.8	5.3	436	3.40	8.1	187.1	13.8	175	0.5	0.5	<0.1	20	0.13
1419155	Rock	3.14	0.412	2.4	11.0	36.5	14	1.3	2.5	4.2	175	1.74	3.1	434.2	4.7	135	0.4	0.3	0.2	3	0.09
1419156	Rock	3.42	0.088	2.6	12.3	12.3	17	0.4	1.3	2.1	667	1.41	3.7	92.4	10.1	58	0.2	1.1	<0.1	5	0.03
1419157	Rock	3.17	0.037	1.4	10.6	8.8	22	0.1	1.7	2.1	299	1.72	3.2	31.4	15.7	52	<0.1	1.6	0.2	9	0.06
1419158	Rock	3.55	0.017	2.0	14.6	12.3	41	<0.1	2.4	2.9	395	2.08	3.3	16.9	15.5	78	<0.1	1.4	0.3	13	0.15
1419159	Rock	3.14	0.017	1.7	13.1	11.7	36	<0.1	1.5	2.4	596	2.01	5.8	17.8	19.8	83	<0.1	1.2	0.2	18	1.10
1419160	Rock	3.72	0.016	1.5	12.7	11.4	36	<0.1	1.7	2.4	619	2.19	6.6	19.2	19.3	83	<0.1	1.2	0.2	19	1.11
1419161	Rock	3.51	<0.005	1.5	5.3	4.6	32	<0.1	2.4	3.7	637	2.12	1.4	1.8	18.8	69	<0.1	0.5	0.3	12	0.99
1419162	Rock	3.33	0.005	1.7	4.1	4.7	24	<0.1	1.3	2.8	574	1.70	4.9	0.9	16.0	45	<0.1	0.7	0.3	7	0.94
1419163	Rock	3.30	0.009	2.0	8.3	5.4	31	<0.1	1.2	2.9	620	1.99	6.5	7.2	17.5	61	<0.1	0.9	0.4	7	1.27
1419164	Rock	3.47	0.021	1.7	5.4	6.3	34	<0.1	2.2	2.4	618	2.14	3.1	48.5	14.8	97	0.1	0.7	0.2	18	1.88
1419165	Rock	2.91	0.019	1.7	2.4	3.7	25	<0.1	1.0	2.5	520	1.66	2.0	14.2	15.7	117	<0.1	0.4	0.2	12	1.20
1419166	Rock	3.65	<0.005	1.7	4.5	7.2	35	<0.1	1.0	2.5	512	1.73	2.2	5.3	16.0	96	0.1	1.0	0.4	9	0.87
1419167	Rock	3.09	0.052	1.9	3.1	4.4	54	0.2	1.8	2.1	807	2.43	5.4	49.7	20.8	133	0.7	0.4	<0.1	37	2.32
1419168	Rock	3.32	0.027	1.1	1.9	5.0	38	<0.1	1.2	0.8	991	2.01	0.8	36.0	20.1	288	0.6	0.2	<0.1	36	3.31



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
1419139	Rock	0.047	23	10	0.41	2203	0.012	<20	0.30	0.062	0.18	0.8	0.31	3.1	0.1	0.11	1	<0.5	<0.2
1419140	Rock Pulp	0.065	10	43	0.84	237	0.077	<20	1.48	0.083	0.19	9.3	0.76	4.1	1.3	1.52	5	4.4	0.6
1419141	Rock	0.043	19	10	0.29	703	0.004	<20	0.44	0.050	0.25	1.0	0.30	2.3	0.1	0.23	2	0.7	<0.2
1419142	Rock	0.023	29	11	0.19	604	0.007	<20	0.37	0.050	0.23	1.3	0.21	1.6	0.1	0.15	2	<0.5	<0.2
1419143	Rock	0.032	36	11	0.23	693	0.010	<20	0.44	0.054	0.24	1.9	0.25	1.4	0.1	0.53	2	<0.5	<0.2
1419144	Rock	0.041	18	21	0.18	1778	0.009	<20	0.62	0.069	0.26	0.7	0.13	11.1	0.1	0.05	2	<0.5	0.4
1419145	Rock	0.024	7	15	0.10	2293	<0.001	<20	0.47	0.049	0.24	0.5	0.17	10.4	0.2	0.06	2	1.3	<0.2
1419146	Rock	0.003	1	9	0.03	1027	<0.001	<20	0.34	0.044	0.21	0.5	0.04	1.9	<0.1	<0.05	<1	<0.5	<0.2
1419147	Rock	0.051	13	18	0.14	1716	0.002	<20	0.46	0.079	0.22	0.2	0.10	11.8	0.1	0.06	2	<0.5	<0.2
1419148	Rock	0.113	28	26	0.16	705	0.009	<20	0.62	0.065	0.34	0.1	0.16	16.2	0.2	<0.05	3	<0.5	0.3
1419149	Rock	0.082	25	46	0.85	1161	0.089	<20	1.06	0.070	0.80	0.4	0.13	10.0	0.4	<0.05	7	<0.5	0.3
1419150	Rock	0.016	<1	<1	12.06	41	<0.001	<20	0.02	<0.001	0.02	<0.1	<0.01	0.1	<0.1	<0.05	<1	0.6	<0.2
1419151	Rock	0.012	26	6	0.04	393	0.005	<20	0.24	0.099	0.10	1.2	0.08	5.0	<0.1	<0.05	1	<0.5	<0.2
1419152	Rock	0.006	19	5	0.03	1175	0.002	<20	0.23	0.124	0.06	2.0	0.06	4.5	<0.1	<0.05	1	<0.5	<0.2
1419153	Rock	0.017	29	5	0.02	998	0.002	<20	0.20	0.128	0.05	0.7	0.09	4.6	<0.1	<0.05	<1	<0.5	0.2
1419154	Rock	0.057	15	7	0.03	3959	0.002	<20	0.37	0.141	0.07	0.4	0.15	7.1	<0.1	0.15	1	<0.5	0.6
1419155	Rock	0.016	5	6	0.03	3644	<0.001	<20	0.25	0.038	0.10	2.9	0.16	2.3	<0.1	0.16	<1	<0.5	1.3
1419156	Rock	0.007	10	6	0.02	1196	<0.001	<20	0.20	0.084	0.06	2.8	0.15	2.1	<0.1	<0.05	<1	<0.5	<0.2
1419157	Rock	0.013	28	5	0.03	1166	0.003	<20	0.24	0.087	0.11	1.7	0.13	3.0	<0.1	<0.05	1	<0.5	<0.2
1419158	Rock	0.019	28	6	0.04	2213	0.003	<20	0.32	0.082	0.16	0.9	0.11	4.1	<0.1	0.06	2	<0.5	<0.2
1419159	Rock	0.024	30	5	0.11	1493	0.016	<20	0.44	0.068	0.26	1.2	0.07	3.3	0.1	<0.05	2	<0.5	<0.2
1419160	Rock	0.023	29	5	0.11	1355	0.015	<20	0.51	0.091	0.29	0.9	0.09	3.2	0.1	<0.05	2	0.7	<0.2
1419161	Rock	0.028	37	6	0.27	836	0.051	<20	0.67	0.069	0.48	1.9	0.07	1.4	0.3	0.06	4	<0.5	<0.2
1419162	Rock	0.020	31	5	0.11	406	0.015	<20	0.50	0.069	0.28	0.6	0.07	2.7	0.1	<0.05	2	<0.5	<0.2
1419163	Rock	0.030	37	5	0.11	491	0.013	<20	0.49	0.059	0.29	0.9	0.11	3.1	0.1	<0.05	3	<0.5	<0.2
1419164	Rock	0.026	25	6	0.09	1555	0.005	<20	0.48	0.069	0.28	0.8	0.12	2.7	0.1	0.07	2	<0.5	<0.2
1419165	Rock	0.026	24	5	0.14	2264	0.020	<20	0.49	0.067	0.28	1.5	0.12	1.9	0.1	0.08	2	<0.5	<0.2
1419166	Rock	0.018	28	6	0.17	1359	0.026	<20	0.61	0.063	0.38	1.6	0.09	1.3	0.2	0.06	3	<0.5	<0.2
1419167	Rock	0.032	26	6	0.05	2266	0.004	<20	0.24	0.112	0.09	0.6	0.15	4.5	0.1	0.12	<1	<0.5	<0.2
1419168	Rock	0.037	27	5	0.04	2452	0.011	<20	0.22	0.139	0.06	0.7	0.04	4.9	<0.1	0.14	<1	<0.5	0.3



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419169	Rock	3.45	0.188	1.7	3.2	6.4	35	0.6	1.3	2.7	739	2.89	0.9	146.8	17.3	95	0.3	0.2	<0.1	26	1.84
1419170	Rock Pulp	0.12	0.820	4.0	30.5	5.3	50	0.3	21.2	9.4	409	2.56	7.5	582.6	0.9	40	0.1	0.9	0.1	63	0.84
1419171	Rock	3.32	0.149	1.6	3.2	10.1	19	0.5	2.3	2.9	466	2.45	0.9	144.1	17.5	80	0.2	0.2	<0.1	11	1.35
1419172	Rock	3.21	0.064	1.7	3.8	5.0	21	0.2	1.6	2.6	554	2.19	1.9	52.3	19.3	146	0.2	0.2	<0.1	33	2.13
1419173	Rock	3.43	0.084	1.8	3.2	4.4	35	0.4	1.6	2.6	665	2.26	3.2	149.4	19.5	147	0.4	0.3	<0.1	35	2.22
1419174	Rock	3.02	0.038	1.6	3.3	4.2	25	0.2	2.1	2.3	553	1.78	4.8	50.3	15.9	100	0.3	0.4	<0.1	29	1.64
1419175	Rock	3.22	<0.005	1.4	6.7	5.9	33	<0.1	2.6	2.8	546	1.70	5.6	1.4	9.6	111	0.2	0.7	<0.1	44	1.62
1419176	Rock	3.94	<0.005	1.4	2.8	6.8	23	<0.1	1.8	2.4	721	2.61	2.3	7.2	16.8	125	0.3	0.3	<0.1	68	2.29
1419177	Rock	3.56	<0.005	1.9	3.2	7.7	13	<0.1	2.1	1.4	537	1.64	8.8	8.4	17.8	134	0.2	0.2	<0.1	37	2.75
1419178	Rock	3.47	0.007	2.2	9.1	6.0	29	<0.1	10.4	5.8	679	2.23	0.6	5.5	16.9	121	0.2	0.4	0.2	40	2.36
1419179	Rock	3.37	<0.005	2.6	10.9	4.4	35	<0.1	8.1	6.9	501	2.25	2.2	4.7	16.8	74	<0.1	1.0	0.4	27	1.32
1419180	Rock	0.76	<0.005	<0.1	1.7	1.5	15	<0.1	1.4	1.0	222	0.43	<0.5	<0.5	0.2	52	0.1	<0.1	<0.1	<2	22.17
1419181	Rock	3.21	0.007	2.7	5.5	9.0	18	<0.1	2.1	2.7	364	1.54	9.2	5.9	15.2	71	0.1	0.5	0.3	11	0.82
1419182	Rock	3.38	<0.005	1.9	3.9	6.3	21	<0.1	2.3	1.9	616	2.05	39.8	10.4	18.9	96	0.2	0.2	<0.1	36	1.64
1419183	Rock	3.81	0.011	1.6	3.1	6.7	19	<0.1	2.1	2.9	682	2.27	15.4	12.0	19.1	123	0.2	0.2	<0.1	32	1.54
1419184	Rock	3.56	0.016	1.8	4.0	17.6	20	0.1	2.5	4.7	694	2.26	12.1	16.3	16.8	113	0.3	0.2	<0.1	20	1.80
1419185	Rock	3.19	0.009	2.4	4.9	10.4	20	<0.1	1.9	3.7	346	2.15	3.3	5.7	9.6	113	0.2	0.3	0.3	11	1.21
1419186	Rock	3.66	0.007	1.8	4.2	9.2	21	<0.1	2.3	2.6	560	2.52	9.0	8.8	16.9	145	0.2	0.4	<0.1	52	1.37
1419187	Rock	3.37	0.020	3.0	3.9	11.1	32	0.1	2.4	4.8	406	2.45	3.4	13.4	15.9	116	0.1	0.4	0.3	20	1.28
1419188	Rock	3.54	<0.005	1.6	6.8	9.4	30	<0.1	2.5	4.2	666	2.27	4.2	6.0	15.1	193	0.2	1.2	0.3	19	2.77
1419189	Rock	3.66	0.019	1.7	9.5	6.8	32	0.1	2.2	4.8	762	2.53	2.4	16.9	14.3	135	0.2	1.9	0.1	34	2.31
1419190	Rock	3.21	0.019	1.5	9.1	6.6	30	0.1	2.2	4.9	734	2.33	2.2	15.1	13.4	128	0.2	1.8	0.1	29	2.24
1419191	Rock	3.36	0.161	1.8	9.1	14.5	32	<0.1	2.5	3.5	842	2.81	52.1	17.0	14.8	135	0.3	2.1	<0.1	49	2.10
1419192	Rock	3.41	0.020	2.6	3.3	10.6	64	<0.1	5.4	3.7	1174	2.25	25.9	4.0	30.7	159	0.4	0.4	<0.1	37	3.51
1419193	Rock	3.45	<0.005	2.1	5.7	9.0	128	<0.1	22.4	9.4	1165	2.86	3.0	1.7	22.8	218	0.6	0.6	<0.1	74	3.19
1419194	Rock	3.19	<0.005	1.8	21.4	9.5	175	<0.1	57.0	22.0	1678	4.10	0.8	1.0	4.9	272	0.6	0.3	<0.1	121	5.02
1419195	Rock	3.19	0.007	2.5	4.8	8.0	35	<0.1	4.4	3.6	737	2.38	16.0	7.2	15.9	143	0.3	0.5	<0.1	48	2.03
1419196	Rock	3.23	<0.005	4.6	19.9	8.9	52	<0.1	27.0	16.7	947	3.50	8.1	5.4	10.1	245	0.2	0.7	0.2	53	3.26
1419197	Rock	3.16	0.005	3.0	9.2	10.0	56	<0.1	13.7	7.2	1112	2.86	12.7	7.0	11.3	239	0.3	0.8	<0.1	45	3.91
1419198	Rock	3.01	0.043	2.0	4.2	17.6	26	0.2	4.2	3.4	1014	2.75	58.4	32.2	16.0	201	0.4	0.6	<0.1	44	2.56



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 3 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
1419169	Rock	0.049	15	6	0.25	363	0.004	<20	0.19	0.123	0.04	1.7	0.18	6.9	<0.1	0.83	<1	<0.5	0.3
1419170	Rock Pulp	0.060	4	30	0.75	95	0.117	<20	1.57	0.090	0.14	10.6	0.06	4.9	<0.1	<0.05	5	<0.5	<0.2
1419171	Rock	0.037	14	7	0.18	136	0.001	<20	0.17	0.140	0.03	2.7	0.24	3.7	<0.1	1.35	<1	<0.5	0.3
1419172	Rock	0.033	20	5	0.35	506	0.006	<20	0.19	0.126	0.05	1.3	0.20	3.2	<0.1	0.61	<1	<0.5	0.2
1419173	Rock	0.033	18	6	0.28	592	0.006	<20	0.17	0.122	0.04	1.0	0.28	4.2	<0.1	0.58	<1	<0.5	0.3
1419174	Rock	0.025	15	6	0.29	658	0.007	<20	0.20	0.131	0.07	1.2	0.35	3.7	<0.1	0.50	<1	<0.5	<0.2
1419175	Rock	0.024	17	7	0.23	964	0.011	<20	0.20	0.069	0.10	5.2	2.65	3.2	<0.1	0.06	1	<0.5	<0.2
1419176	Rock	0.030	32	6	0.34	1512	0.003	<20	0.19	0.111	0.05	1.3	3.64	5.5	<0.1	0.07	<1	<0.5	<0.2
1419177	Rock	0.030	27	7	0.24	1475	0.002	<20	0.14	0.099	0.03	0.7	5.82	4.0	<0.1	0.08	<1	<0.5	<0.2
1419178	Rock	0.036	32	19	0.66	899	0.028	<20	0.52	0.098	0.36	0.9	7.32	7.2	0.1	0.12	2	<0.5	<0.2
1419179	Rock	0.039	30	22	0.64	449	0.049	<20	0.75	0.049	0.60	1.7	2.38	6.1	0.3	0.14	3	<0.5	<0.2
1419180	Rock	0.016	<1	<1	10.91	38	<0.001	<20	0.01	0.001	0.01	<0.1	0.02	0.3	<0.1	<0.05	<1	<0.5	<0.2
1419181	Rock	0.022	28	7	0.19	844	0.003	<20	0.29	0.077	0.17	1.6	4.09	4.2	<0.1	0.16	1	<0.5	<0.2
1419182	Rock	0.023	23	7	0.51	1388	0.002	<20	0.16	0.088	0.05	0.7	6.33	5.3	<0.1	0.20	<1	0.6	<0.2
1419183	Rock	0.030	24	7	0.52	1745	0.001	<20	0.20	0.123	0.05	0.5	4.57	6.0	<0.1	0.30	<1	0.6	<0.2
1419184	Rock	0.024	19	7	0.61	520	<0.001	<20	0.17	0.087	0.06	1.5	4.16	6.2	<0.1	0.82	<1	0.6	<0.2
1419185	Rock	0.012	12	6	0.30	1107	<0.001	<20	0.42	0.036	0.27	0.9	1.22	4.9	<0.1	0.60	1	0.9	<0.2
1419186	Rock	0.036	25	8	0.42	1654	0.009	<20	0.15	0.107	0.04	0.9	1.60	4.9	<0.1	0.36	<1	<0.5	<0.2
1419187	Rock	0.028	22	8	0.38	767	0.003	<20	0.33	0.075	0.21	2.1	1.20	4.7	<0.1	0.88	2	0.7	<0.2
1419188	Rock	0.042	21	8	0.55	1356	0.005	<20	0.36	0.046	0.25	1.6	1.51	4.9	<0.1	0.42	1	<0.5	<0.2
1419189	Rock	0.055	24	7	0.65	1232	0.012	<20	0.35	0.080	0.25	1.3	0.44	5.4	<0.1	0.43	1	<0.5	<0.2
1419190	Rock	0.054	23	7	0.63	1198	0.010	<20	0.28	0.060	0.22	1.3	0.41	5.6	<0.1	0.40	1	<0.5	<0.2
1419191	Rock	0.047	18	8	0.73	1104	0.005	<20	0.25	0.090	0.12	0.8	4.76	6.7	<0.1	0.35	<1	<0.5	<0.2
1419192	Rock	0.020	19	11	1.23	1020	0.002	<20	0.20	0.072	0.10	0.7	2.74	8.8	<0.1	0.10	<1	<0.5	<0.2
1419193	Rock	0.038	29	53	1.78	1719	0.106	<20	1.15	0.101	1.05	0.9	1.00	10.9	0.4	0.05	5	<0.5	<0.2
1419194	Rock	0.073	10	106	2.92	1882	0.211	<20	1.96	0.045	2.07	0.4	0.26	15.2	0.8	0.12	9	<0.5	<0.2
1419195	Rock	0.041	26	12	0.65	1966	0.010	<20	0.23	0.114	0.09	1.1	1.96	5.3	<0.1	0.21	<1	<0.5	<0.2
1419196	Rock	0.063	19	40	1.30	1062	0.048	<20	0.87	0.047	0.68	0.4	0.28	10.1	0.3	0.18	3	0.9	<0.2
1419197	Rock	0.060	19	17	1.04	1889	0.009	<20	0.44	0.067	0.27	0.6	0.95	9.3	0.1	0.14	1	0.7	<0.2
1419198	Rock	0.044	16	9	0.69	2202	0.002	<20	0.24	0.065	0.10	0.3	4.31	7.1	<0.1	0.30	<1	2.0	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 4 of 5 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419199	Rock	3.31	0.073	1.7	5.5	15.6	42	0.2	2.1	5.9	883	3.00	25.6	36.2	14.7	156	0.3	0.5	0.2	38	2.32
1419200	Rock Pulp	0.12	2.281	64.4	2243.5	1321.4	3880	26.7	190.8	21.0	656	5.15	1249.1	5598.7	2.8	85	20.3	15.3	10.4	57	1.52
1419201	Rock	3.08	<0.005	1.8	4.4	13.4	25	<0.1	2.3	2.7	958	2.27	6.4	2.3	18.2	298	0.4	0.5	<0.1	50	3.92
1419202	Rock	3.32	0.054	1.8	3.9	10.0	26	<0.1	1.8	2.8	1051	2.40	47.6	44.3	20.7	139	0.3	0.7	<0.1	44	3.23
1419203	Rock	3.35	0.025	2.4	18.1	17.4	48	<0.1	1.7	5.9	939	2.78	24.9	26.7	15.6	284	0.3	0.7	<0.1	31	3.62
1419204	Rock	3.58	0.114	2.3	6.3	20.2	37	0.2	2.1	4.6	779	2.81	20.8	82.0	15.8	120	0.1	0.9	0.2	24	1.88
1419205	Rock	3.38	0.396	4.5	5.0	9.2	30	0.1	2.4	3.2	976	2.53	20.4	98.0	14.3	164	0.3	0.6	0.2	43	2.98
1419206	Rock	3.42	0.023	2.4	3.5	15.4	26	<0.1	2.1	3.2	897	2.22	9.2	50.0	15.8	185	0.2	0.4	<0.1	38	2.90
1419207	Rock	3.11	0.103	1.9	3.9	11.6	31	<0.1	2.8	4.2	1087	2.49	30.0	59.4	13.2	178	0.3	0.6	0.1	40	3.06
1419208	Rock	2.69	0.010	1.9	2.9	5.3	25	<0.1	1.8	2.5	618	2.20	25.3	11.8	13.3	116	<0.1	1.1	0.7	10	2.04
1419209	Rock	3.30	<0.005	3.2	4.1	6.6	30	<0.1	2.0	2.8	570	1.80	3.3	2.8	14.1	109	<0.1	0.8	0.4	15	2.12
1419210	Rock Pulp	0.12	0.826	4.2	30.8	5.6	49	0.2	23.9	8.5	414	2.61	6.2	300.8	0.9	40	0.3	1.0	0.1	61	0.87
1419211	Rock	2.95	<0.005	3.1	3.8	12.9	44	<0.1	1.6	3.2	1154	1.80	2.4	3.1	15.4	215	0.3	0.5	<0.1	39	4.45
1419212	Rock	3.31	<0.005	2.8	5.4	9.0	48	<0.1	2.9	3.2	1028	1.90	1.7	2.7	17.8	202	0.2	0.5	<0.1	40	4.12
1419213	Rock	3.46	0.005	2.2	3.3	15.2	39	<0.1	1.9	2.6	1196	1.72	4.7	1.5	16.3	225	0.4	0.4	<0.1	34	4.95
1419214	Rock	3.42	<0.005	1.8	4.3	13.1	26	<0.1	2.6	3.0	860	1.55	3.2	0.5	15.4	134	0.2	0.6	0.2	22	3.38
1419215	Rock	3.37	0.011	2.5	2.7	8.5	27	<0.1	2.4	2.9	1023	1.83	1.4	8.8	13.7	166	0.3	0.4	<0.1	36	4.14
1419216	Rock	3.54	0.043	2.7	7.0	8.3	52	<0.1	16.7	8.3	944	2.82	1.3	7.8	8.9	156	<0.1	0.6	<0.1	52	3.86
1411857	Rock	1.78	<0.005	0.9	58.1	11.7	48	<0.1	4.8	8.9	723	2.42	4.6	<0.5	16.0	23	0.3	0.4	0.1	54	0.17
1411858	Rock	1.65	0.080	5.8	21.5	551.9	44	1.8	3.7	3.4	210	2.32	12.2	81.7	1.4	12	0.7	0.3	6.6	21	0.07
1411859	Rock	2.22	<0.005	1.3	17.1	124.2	44	0.2	3.9	4.5	758	1.74	2.7	0.6	10.2	16	0.8	0.1	1.6	16	0.10
1411860	Rock	2.40	0.063	27.7	23.3	744.4	90	4.7	2.9	2.2	85	1.70	7.1	64.9	1.4	10	1.0	0.4	14.8	23	0.02
1411861	Rock	2.01	0.095	1.8	11.5	27.3	38	0.2	4.4	4.7	372	2.07	112.7	88.6	9.5	11	0.3	0.5	0.5	15	0.09
1411862	Rock	1.77	0.101	1.3	5.9	42.7	18	0.2	2.2	1.6	231	1.39	87.6	104.9	6.2	9	0.2	0.4	0.5	9	0.03
1411863	Rock	1.42	0.025	14.3	42.6	210.1	44	1.6	3.0	5.7	423	2.51	9.9	32.1	10.3	35	0.6	0.4	6.6	6	0.11
1411864	Rock	0.73	0.124	1.4	5.4	17.3	7	0.4	1.6	1.0	61	1.22	2.7	146.8	8.3	153	<0.1	1.3	0.2	4	0.12
1411865	Rock	0.87	0.025	0.9	3.6	10.2	7	<0.1	2.0	0.6	68	0.63	22.4	29.3	0.4	110	<0.1	2.1	<0.1	<2	0.07
1411866	Rock	0.90	0.038	0.6	3.8	33.2	7	0.1	1.2	0.7	51	0.98	5.4	37.6	4.8	153	0.1	0.9	<0.1	3	0.06
1411867	Rock	0.88	0.009	1.6	6.9	17.8	15	<0.1	1.7	1.8	100	1.47	2.4	16.0	8.1	148	0.2	0.5	<0.1	3	0.05
1411868	Rock	1.00	0.294	1.6	23.5	35.9	12	0.8	2.9	5.3	56	2.23	3.6	378.7	19.9	42	0.2	1.3	0.3	9	0.20



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 4 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1419199	Rock	0.066	17	8	0.68	786	0.005	<20	0.36	0.074	0.19	0.4	1.63	7.8	<0.1	0.76	1	1.0	0.2
1419200	Rock Pulp	0.057	11	47	0.88	266	0.089	<20	1.54	0.082	0.20	8.6	0.78	4.3	1.4	1.49	6	4.2	0.7
1419201	Rock	0.072	17	10	0.54	2883	0.014	<20	0.17	0.079	0.07	0.8	0.43	6.9	<0.1	0.19	<1	<0.5	<0.2
1419202	Rock	0.055	23	9	0.70	954	0.005	<20	0.21	0.094	0.08	0.4	2.58	7.2	<0.1	0.26	<1	1.2	<0.2
1419203	Rock	0.080	12	8	0.57	1177	0.003	<20	0.31	0.060	0.18	1.8	0.85	7.2	<0.1	0.51	1	<0.5	<0.2
1419204	Rock	0.063	24	8	0.57	837	0.010	<20	0.44	0.068	0.22	0.6	0.48	6.4	<0.1	0.76	2	0.5	<0.2
1419205	Rock	0.075	18	11	0.78	1201	0.011	<20	0.20	0.093	0.08	0.8	0.40	8.2	<0.1	0.44	<1	<0.5	<0.2
1419206	Rock	0.051	22	10	0.63	1588	0.010	<20	0.20	0.129	0.05	0.8	0.82	7.7	<0.1	0.45	<1	<0.5	<0.2
1419207	Rock	0.064	16	9	0.84	1643	0.006	<20	0.24	0.078	0.13	4.2	0.77	6.9	<0.1	0.45	<1	<0.5	<0.2
1419208	Rock	0.070	35	8	0.41	131	0.012	<20	0.82	0.034	0.47	0.5	0.10	3.5	0.2	0.26	3	<0.5	<0.2
1419209	Rock	0.067	27	10	0.44	270	0.026	<20	0.67	0.050	0.42	0.7	0.10	4.8	0.2	0.13	3	<0.5	<0.2
1419210	Rock Pulp	0.054	4	30	0.77	94	0.125	<20	1.60	0.089	0.13	10.2	0.03	4.6	<0.1	<0.05	5	<0.5	<0.2
1419211	Rock	0.057	24	11	0.56	330	0.019	<20	0.32	0.094	0.19	0.6	0.20	6.3	<0.1	0.09	1	<0.5	<0.2
1419212	Rock	0.065	30	13	0.65	543	0.024	<20	0.33	0.093	0.20	1.1	0.17	5.7	<0.1	<0.05	1	0.7	<0.2
1419213	Rock	0.076	22	11	0.63	577	0.010	<20	0.35	0.086	0.21	1.0	0.41	6.8	<0.1	0.08	1	<0.5	<0.2
1419214	Rock	0.056	20	11	0.59	653	0.007	<20	0.28	0.080	0.16	1.4	0.22	5.0	<0.1	0.10	1	<0.5	<0.2
1419215	Rock	0.055	18	12	0.65	653	0.014	<20	0.33	0.097	0.21	0.7	0.10	6.0	<0.1	0.11	1	<0.5	<0.2
1419216	Rock	0.063	13	31	1.32	1246	0.049	<20	0.69	0.085	0.53	1.3	0.15	9.9	0.2	0.34	3	<0.5	<0.2
1411857	Rock	0.047	17	7	0.20	137	0.021	<20	0.59	0.041	0.36	0.2	0.02	3.7	<0.1	<0.05	4	<0.5	<0.2
1411858	Rock	0.027	5	6	0.03	49	0.003	<20	0.19	0.007	0.13	0.1	0.02	0.7	<0.1	<0.05	<1	0.5	1.0
1411859	Rock	0.033	22	4	0.05	99	0.004	<20	0.31	0.011	0.22	0.1	0.02	3.4	<0.1	<0.05	1	0.7	<0.2
1411860	Rock	0.016	10	5	0.01	27	0.001	<20	0.07	0.004	0.06	0.2	0.07	0.3	<0.1	<0.05	<1	0.6	0.4
1411861	Rock	0.031	30	5	0.05	81	0.001	<20	0.38	0.008	0.24	0.1	0.02	3.7	<0.1	<0.05	1	<0.5	0.7
1411862	Rock	0.004	12	3	0.03	63	0.002	<20	0.30	0.045	0.22	0.1	0.03	1.3	<0.1	<0.05	<1	<0.5	0.4
1411863	Rock	0.010	45	4	0.02	1468	0.002	<20	0.17	0.007	0.17	<0.1	<0.01	1.8	<0.1	<0.05	<1	0.6	0.2
1411864	Rock	0.010	24	3	0.02	4078	<0.001	<20	0.25	0.105	0.07	<0.1	0.82	1.7	<0.1	0.15	<1	0.5	0.2
1411865	Rock	<0.001	4	4	<0.01	4090	<0.001	<20	0.03	0.002	<0.01	0.2	0.29	0.6	<0.1	0.13	<1	<0.5	<0.2
1411866	Rock	0.010	7	2	<0.01	4107	<0.001	<20	0.29	0.153	0.08	0.3	0.14	1.6	<0.1	0.14	1	1.1	<0.2
1411867	Rock	0.009	8	2	0.01	4016	<0.001	<20	0.21	0.127	0.04	0.2	0.11	1.0	<0.1	0.14	<1	<0.5	<0.2
1411868	Rock	0.016	46	4	0.01	1030	0.002	<20	0.25	0.185	0.02	0.1	0.05	3.2	<0.1	<0.05	<1	0.7	1.8



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 5 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1411869	Rock	0.88	0.055	1.3	5.7	16.5	67	0.3	3.0	4.8	363	2.32	5.1	52.7	8.8	72	<0.1	0.8	<0.1	31	0.20
1411870	Rock	0.83	<0.005	2.5	5.6	24.1	37	0.1	1.9	2.0	369	2.05	8.7	9.2	16.8	79	0.3	0.8	<0.1	22	0.11
1411871	Rock	0.88	0.148	1.2	6.4	8.1	8	0.6	1.9	0.8	93	0.74	80.7	152.3	0.8	174	<0.1	3.3	<0.1	<2	0.04
1411872	Rock	0.92	<0.005	1.1	4.8	3.9	36	<0.1	2.9	2.0	923	2.20	45.4	1.8	21.0	20	0.3	2.8	<0.1	54	0.11
1411873	Rock	0.80	0.011	0.5	115.8	5.1	64	0.9	12.1	5.6	402	1.86	3.5	10.4	7.3	26	<0.1	0.2	<0.1	36	0.18



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 5 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000259.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1411869	Rock	0.043	25	6	0.02	2415	0.001	<20	0.29	0.102	0.10	<0.1	0.02	9.3	<0.1	0.06	1	<0.5	<0.2
1411870	Rock	0.031	33	2	0.02	3088	0.001	<20	0.31	0.165	0.07	0.4	0.35	4.7	<0.1	0.11	<1	<0.5	0.2
1411871	Rock	0.002	3	4	<0.01	4138	<0.001	<20	0.10	0.015	0.04	0.3	0.34	1.1	<0.1	0.14	<1	<0.5	0.5
1411872	Rock	0.039	36	2	0.01	619	0.017	<20	0.26	0.172	0.04	1.2	0.10	3.9	<0.1	<0.05	<1	<0.5	<0.2
1411873	Rock	0.036	21	10	0.45	516	0.049	<20	1.01	0.046	0.56	0.2	0.07	5.6	0.2	<0.05	4	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 1 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000259.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1419149	Rock	2.85	0.006	1.3	9.9	4.9	88	<0.1	11.8	9.8	495	3.01	3.0	2.6	9.4	57	0.2	0.9	0.6	73	0.31
REP 1419149	QC	0.005																			
1419170	Rock Pulp	0.12	0.820	4.0	30.5	5.3	50	0.3	21.2	9.4	409	2.56	7.5	582.6	0.9	40	0.1	0.9	0.1	63	0.84
REP 1419170	QC	3.9 31.9 5.1 51 0.2 22.7 8.9 408 2.57 6.4 402.3 0.9 41 0.1 0.8 0.1 62 0.85																			
1419171	Rock	3.32	0.149	1.6	3.2	10.1	19	0.5	2.3	2.9	466	2.45	0.9	144.1	17.5	80	0.2	0.2	<0.1	11	1.35
REP 1419171	QC	0.143																			
1419203	Rock	3.35	0.025	2.4	18.1	17.4	48	<0.1	1.7	5.9	939	2.78	24.9	26.7	15.6	284	0.3	0.7	<0.1	31	3.62
REP 1419203	QC	2.5 16.9 17.6 45 <0.1 1.7 5.6 923 2.70 24.6 22.9 14.9 278 0.2 0.7 <0.1 30 3.51																			
1411862	Rock	1.77	0.101	1.3	5.9	42.7	18	0.2	2.2	1.6	231	1.39	87.6	104.9	6.2	9	0.2	0.4	0.5	9	0.03
REP 1411862	QC	0.101																			
1411873	Rock	0.80	0.011	0.5	115.8	5.1	64	0.9	12.1	5.6	402	1.86	3.5	10.4	7.3	26	<0.1	0.2	<0.1	36	0.18
REP 1411873	QC	0.5 114.5 5.2 63 0.9 11.3 5.6 397 1.83 4.1 11.5 7.0 26 0.1 0.2 <0.1 36 0.18																			
Core Reject Duplicates																					
1419146	Rock	2.95	0.025	3.7	5.6	7.3	15	<0.1	16.5	1.6	241	1.27	5.2	22.2	0.7	46	<0.1	0.9	<0.1	10	0.39
DUP 1419146	QC	0.028 3.1 5.4 7.6 17 <0.1 12.4 1.5 233 1.22 5.1 18.9 0.8 45 0.1 0.7 <0.1 10 0.40																			
1419180	Rock	0.76	<0.005	<0.1	1.7	1.5	15	<0.1	1.4	1.0	222	0.43	<0.5	<0.5	0.2	52	0.1	<0.1	<0.1	<2	22.17
DUP 1419180	QC	<0.005 <0.1 1.5 1.3 15 <0.1 1.7 0.7 217 0.41 <0.5 <0.5 0.1 49 <0.1 <0.1 <0.1 <2 21.66																			
1419214	Rock	3.42	<0.005	1.8	4.3	13.1	26	<0.1	2.6	3.0	860	1.55	3.2	0.5	15.4	134	0.2	0.6	0.2	22	3.38
DUP 1419214	QC	<0.005 2.3 4.3 12.9 24 <0.1 2.0 2.8 874 1.60 2.5 3.8 15.8 132 <0.1 0.6 0.2 24 3.42																			
Reference Materials																					
STD DS10	Standard	14.6 141.9 152.8 370 1.8 71.7 11.2 903 2.82 43.9 57.2 7.6 69 2.6 8.5 14.7 42 1.09																			
STD DS10	Standard	14.0 146.4 153.3 371 2.2 71.6 12.3 896 2.81 50.0 47.5 7.3 68 2.4 8.1 14.7 45 1.08																			
STD DS10	Standard	14.9 173.3 158.3 365 1.8 77.1 13.0 926 2.79 48.7 51.0 8.3 67 3.1 7.7 14.1 43 1.10																			
STD OREAS45EA	Standard	1.6 716.7 13.7 34 0.2 396.5 53.2 439 24.38 12.7 50.3 9.6 4 0.1 0.3 0.3 335 0.04																			
STD OREAS45EA	Standard	1.6 718.4 13.4 35 0.2 400.4 51.3 421 22.30 11.9 53.9 9.6 4 <0.1 0.3 0.3 315 0.03																			
STD OREAS45EA	Standard	1.7 736.9 16.6 34 0.3 412.5 57.1 449 25.01 12.6 52.6 10.7 4 <0.1 0.3 0.3 347 0.04																			
STD OXD108	Standard	0.403																			
STD OXD108	Standard	0.411																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000259.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1419149	Rock	0.082	25	46	0.85	1161	0.089	<20	1.06	0.070	0.80	0.4	0.13	10.0	0.4	<0.05	7	<0.5	0.3
REP 1419149	QC																		
1419170	Rock Pulp	0.060	4	30	0.75	95	0.117	<20	1.57	0.090	0.14	10.6	0.06	4.9	<0.1	<0.05	5	<0.5	<0.2
REP 1419170	QC	0.054	4	30	0.74	100	0.118	<20	1.55	0.090	0.14	10.6	0.04	5.2	<0.1	<0.05	5	<0.5	<0.2
1419171	Rock	0.037	14	7	0.18	136	0.001	<20	0.17	0.140	0.03	2.7	0.24	3.7	<0.1	1.35	<1	<0.5	0.3
REP 1419171	QC																		
1419203	Rock	0.080	12	8	0.57	1177	0.003	<20	0.31	0.060	0.18	1.8	0.85	7.2	<0.1	0.51	1	<0.5	<0.2
REP 1419203	QC	0.070	12	8	0.55	1296	0.003	<20	0.30	0.058	0.18	2.3	0.85	7.2	<0.1	0.51	1	<0.5	<0.2
1411862	Rock	0.004	12	3	0.03	63	0.002	<20	0.30	0.045	0.22	0.1	0.03	1.3	<0.1	<0.05	<1	<0.5	0.4
REP 1411862	QC																		
1411873	Rock	0.036	21	10	0.45	516	0.049	<20	1.01	0.046	0.56	0.2	0.07	5.6	0.2	<0.05	4	<0.5	<0.2
REP 1411873	QC	0.034	21	11	0.44	501	0.050	<20	1.01	0.046	0.56	0.2	0.08	5.8	0.2	<0.05	5	<0.5	<0.2
Core Reject Duplicates																			
1419146	Rock	0.003	1	9	0.03	1027	<0.001	<20	0.34	0.044	0.21	0.5	0.04	1.9	<0.1	<0.05	<1	<0.5	<0.2
DUP 1419146	QC	0.003	1	8	0.03	1005	<0.001	<20	0.33	0.043	0.21	0.4	0.05	2.0	0.1	<0.05	<1	<0.5	<0.2
1419180	Rock	0.016	<1	<1	10.91	38	<0.001	<20	0.01	0.001	0.01	<0.1	0.02	0.3	<0.1	<0.05	<1	<0.5	<0.2
DUP 1419180	QC	0.014	<1	<1	10.71	39	0.001	<20	0.02	0.002	0.01	<0.1	0.03	0.3	<0.1	<0.05	<1	<0.5	<0.2
1419214	Rock	0.056	20	11	0.59	653	0.007	<20	0.28	0.080	0.16	1.4	0.22	5.0	<0.1	0.10	1	<0.5	<0.2
DUP 1419214	QC	0.056	21	11	0.60	651	0.008	<20	0.32	0.105	0.18	1.1	0.24	5.3	<0.1	0.10	1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.077	17	52	0.79	417	0.077	<20	1.07	0.072	0.35	3.2	0.29	3.3	5.2	0.28	4	2.6	6.5
STD DS10	Standard	0.079	17	52	0.79	414	0.074	<20	1.06	0.074	0.34	2.9	0.29	2.8	5.2	0.29	4	1.2	5.4
STD DS10	Standard	0.077	19	58	0.82	405	0.089	<20	1.09	0.073	0.35	3.2	0.30	3.0	5.5	0.29	4	2.0	5.0
STD OREAS45EA	Standard	0.032	7	906	0.11	140	0.105	<20	3.23	0.020	0.05	<0.1	0.03	85.8	<0.1	<0.05	13	0.7	0.2
STD OREAS45EA	Standard	0.033	7	871	0.11	136	0.096	<20	3.35	0.025	0.06	<0.1	0.01	88.4	<0.1	<0.05	12	1.3	<0.2
STD OREAS45EA	Standard	0.029	9	893	0.10	168	0.110	<20	3.40	0.020	0.05	<0.1	0.02	82.3	<0.1	<0.05	13	1.3	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 2 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000259.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OXD108	Standard	0.399																			
STD OXI121	Standard	1.747																			
STD OXI121	Standard	1.792																			
STD OXI121	Standard	1.772																			
STD OXN117	Standard	7.465																			
STD OXN117	Standard	7.548																			
STD OXN117	Standard	7.142																			
STD DS10 Expected			13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected			1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
STD OXD108 Expected		0.414																			
STD OXN117 Expected		7.679																			
STD OXI121 Expected		1.834																			
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	0.020																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.7	3.2	1.3	29	<0.1	1.1	3.0	428	1.78	0.9	0.5	2.2	26	<0.1	<0.1	<0.1	23	0.60	
ROCK-WHI	Prep Blank	<0.005	0.7	2.6	1.4	27	<0.1	1.0	3.2	434	1.79	0.8	1.5	2.3	28	<0.1	<0.1	<0.1	24	0.64	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 21, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000259.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXD108	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	3	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.039	5	3	0.38	72	0.073	<20	0.99	0.155	0.14	0.2	<0.01	2.3	<0.1	<0.05	3	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.035	5	3	0.38	79	0.077	<20	1.09	0.181	0.16	0.2	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 09, 2016
Report Date: September 22, 2016
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI16000268.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-07-Rock
P.O. Number
Number of Samples: 70

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	67	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	70	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	70	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	70	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 2 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162501	Rock	2.49	0.099	3.3	13.1	45.0	66	0.1	6.5	6.6	722	2.91	29.4	87.3	18.1	83	0.5	2.4	0.2	31	0.51
1162502	Rock	3.90	0.132	3.1	5.7	62.3	90	0.2	4.4	8.8	1093	2.60	23.5	134.6	14.3	87	0.6	2.5	0.1	20	0.09
1162503	Rock	4.50	0.044	1.4	7.4	47.0	83	<0.1	4.6	3.0	162	3.32	13.8	39.7	8.5	117	0.3	1.0	<0.1	27	0.10
1162504	Rock	3.63	0.028	2.5	12.5	34.3	104	<0.1	7.0	10.6	2454	3.62	20.4	24.7	7.7	142	0.7	2.3	<0.1	22	0.10
1162505	Rock	2.06	0.026	3.9	25.3	40.0	57	0.1	4.7	6.6	2120	3.09	13.8	33.5	6.5	90	1.1	2.8	0.3	14	0.10
1162506	Rock	2.34	0.059	2.9	25.2	12.7	46	<0.1	2.2	5.6	995	2.70	8.5	6.7	18.7	46	0.2	5.7	0.2	13	0.10
1162507	Rock	2.61	0.006	2.2	18.1	7.8	48	<0.1	2.5	4.4	520	2.67	2.6	2.4	15.1	47	<0.1	4.4	0.2	17	0.15
1162508	Rock	2.23	0.010	1.5	17.2	8.8	57	<0.1	2.6	5.0	505	2.67	2.6	9.0	16.1	28	0.2	1.4	0.1	27	0.21
1162509	Rock	2.49	0.007	1.6	18.7	8.0	53	<0.1	2.0	4.9	573	2.34	5.3	5.9	16.1	42	0.2	4.5	<0.1	21	0.15
1162510	Rock Pulp	0.12	0.807	3.6	30.5	5.0	47	0.3	23.5	8.8	393	2.57	6.1	1188.7	0.9	42	0.2	1.0	0.1	60	0.87
1162511	Rock	3.06	0.005	1.4	16.1	7.7	56	<0.1	4.7	5.4	532	2.57	5.4	0.9	15.4	33	0.1	4.6	0.2	21	0.16
1162512	Rock	2.80	0.006	1.7	17.3	8.0	50	<0.1	3.7	4.8	549	2.46	3.0	3.8	17.3	25	<0.1	4.1	0.2	17	0.15
1162513	Rock	2.75	<0.005	1.3	10.2	7.2	47	<0.1	1.8	3.9	512	2.25	2.0	3.0	17.5	21	<0.1	3.5	0.1	14	0.15
1162514	Rock	3.22	<0.005	1.3	6.6	8.5	31	<0.1	1.7	2.9	263	1.95	1.9	0.8	15.8	31	<0.1	2.6	<0.1	13	0.13
1162515	Rock	2.91	<0.005	1.3	4.3	9.9	46	<0.1	2.4	3.3	412	2.02	1.9	<0.5	17.1	35	0.1	1.2	<0.1	29	0.14
1162516	Rock	3.17	<0.005	1.1	3.4	9.7	47	<0.1	1.9	3.0	483	1.93	2.0	1.3	17.8	46	0.2	1.7	<0.1	21	0.13
1162517	Rock	2.60	<0.005	1.5	2.6	16.4	91	<0.1	2.2	4.6	973	2.79	4.7	1.5	18.3	33	0.4	1.1	<0.1	58	0.17
1162518	Rock	2.11	<0.005	1.3	5.0	19.1	73	<0.1	1.8	3.3	1047	2.26	3.7	<0.5	22.2	99	0.5	2.1	<0.1	48	0.17
1162519	Rock	2.72	<0.005	1.3	2.0	10.0	59	<0.1	1.4	2.4	669	1.83	1.5	<0.5	20.4	34	0.3	0.9	<0.1	48	0.17
1162520	Rock	0.73	<0.005	0.1	2.3	1.5	16	<0.1	1.1	0.6	240	0.51	<0.5	<0.5	0.4	45	<0.1	<0.1	<0.1	2	22.33
1162521	Rock	2.90	<0.005	1.1	3.1	12.4	98	<0.1	1.9	4.3	898	2.86	3.3	<0.5	16.1	83	0.4	0.9	<0.1	59	2.42
1162522	Rock	2.86	0.009	1.0	17.6	11.0	110	<0.1	1.5	5.6	607	3.50	3.5	6.7	15.1	78	0.2	4.2	<0.1	47	0.43
1162523	Rock	2.59	0.006	1.0	9.1	25.6	98	<0.1	1.4	4.3	835	3.09	6.0	3.8	15.3	56	0.3	3.1	0.1	53	0.22
1162524	Rock	2.59	0.006	1.3	26.6	11.6	83	<0.1	1.8	4.5	896	2.82	10.2	4.4	15.8	105	0.3	8.9	<0.1	49	1.15
1162525	Rock	2.40	<0.005	1.3	17.1	12.7	69	<0.1	1.5	3.6	689	2.32	4.8	<0.5	17.4	181	0.2	6.3	0.1	30	1.72
1162526	Rock	3.16	<0.005	1.9	5.6	6.0	42	<0.1	1.8	3.4	469	2.16	3.6	<0.5	18.0	64	<0.1	2.7	<0.1	14	1.06
1162527	Rock	2.48	<0.005	1.7	7.7	5.1	55	<0.1	1.6	3.5	510	2.11	2.8	2.0	16.2	131	0.1	3.1	<0.1	31	1.38
1162528	Rock	3.26	0.007	1.3	18.6	9.0	70	<0.1	1.6	4.4	822	2.41	4.7	2.2	18.2	239	0.3	6.6	<0.1	37	3.26
1162529	Rock	3.03	<0.005	1.7	17.1	5.8	44	<0.1	1.5	3.8	519	2.28	4.4	<0.5	18.5	105	<0.1	7.3	<0.1	20	1.11
1162530	Rock	3.64	<0.005	1.6	18.3	5.8	42	<0.1	1.5	3.8	486	2.16	4.3	<0.5	17.5	105	<0.1	7.3	<0.1	20	1.09



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1162501	Rock	0.049	34	10	0.10	2257	0.004	<20	0.57	0.057	0.13	0.6	0.30	7.6	<0.1	0.06	2	<0.5	0.2
1162502	Rock	0.027	29	8	0.05	3343	0.001	<20	0.40	0.043	0.11	0.7	0.72	5.9	0.1	0.08	1	<0.5	0.3
1162503	Rock	0.034	17	8	0.05	2347	<0.001	<20	0.51	0.012	0.28	0.9	0.49	7.4	<0.1	0.11	2	0.7	<0.2
1162504	Rock	0.028	18	6	0.04	3095	<0.001	<20	0.46	0.005	0.27	1.0	0.61	6.5	0.3	0.11	2	<0.5	<0.2
1162505	Rock	0.018	15	4	0.04	3061	<0.001	<20	0.45	0.005	0.23	0.8	0.82	6.1	0.3	0.07	2	<0.5	0.2
1162506	Rock	0.039	46	4	0.16	552	0.015	<20	0.52	0.042	0.31	0.2	0.47	4.0	0.2	0.06	3	0.5	<0.2
1162507	Rock	0.056	33	5	0.20	1177	0.029	<20	0.63	0.055	0.40	0.4	0.41	4.2	0.2	<0.05	4	<0.5	<0.2
1162508	Rock	0.066	43	5	0.42	449	0.079	<20	0.87	0.062	0.59	0.5	0.10	3.9	0.3	<0.05	5	<0.5	<0.2
1162509	Rock	0.055	43	4	0.12	1001	0.021	<20	0.42	0.079	0.22	0.5	0.07	3.7	0.1	<0.05	2	<0.5	<0.2
1162510	Rock Pulp	0.053	4	30	0.72	91	0.128	<20	1.56	0.083	0.13	9.9	0.06	4.9	<0.1	<0.05	5	<0.5	<0.2
1162511	Rock	0.056	43	13	0.26	634	0.037	<20	0.60	0.061	0.41	0.5	0.14	4.0	0.2	<0.05	3	0.6	<0.2
1162512	Rock	0.048	47	8	0.31	507	0.064	<20	0.78	0.060	0.56	0.5	0.21	3.2	0.2	<0.05	4	<0.5	<0.2
1162513	Rock	0.043	42	6	0.29	486	0.075	<20	0.78	0.056	0.59	0.6	0.22	2.5	0.3	<0.05	4	<0.5	<0.2
1162514	Rock	0.039	33	5	0.22	827	0.052	<20	0.58	0.089	0.41	0.9	0.12	2.1	0.2	<0.05	3	<0.5	<0.2
1162515	Rock	0.047	37	6	0.26	1033	0.062	<20	0.58	0.089	0.39	0.8	0.07	3.0	0.2	<0.05	3	0.6	<0.2
1162516	Rock	0.044	41	5	0.07	1322	0.018	<20	0.36	0.086	0.19	0.9	0.03	2.7	<0.1	<0.05	2	<0.5	<0.2
1162517	Rock	0.079	45	5	0.04	1021	0.030	<20	0.27	0.095	0.11	0.9	0.04	6.0	<0.1	<0.05	1	<0.5	<0.2
1162518	Rock	0.082	29	5	0.04	3341	0.019	<20	0.30	0.133	0.10	0.4	0.06	5.8	<0.1	0.08	2	<0.5	<0.2
1162519	Rock	0.056	36	5	0.02	1299	0.031	<20	0.20	0.123	0.06	0.8	0.02	4.9	<0.1	<0.05	<1	<0.5	<0.2
1162520	Rock	0.017	1	<1	12.45	41	0.003	<20	0.06	0.002	0.03	<0.1	<0.01	2.2	<0.1	<0.05	<1	<0.5	<0.2
1162521	Rock	0.055	25	5	0.05	2440	0.010	<20	0.26	0.080	0.09	0.3	0.13	6.4	<0.1	0.06	1	<0.5	<0.2
1162522	Rock	0.072	19	4	0.08	2111	0.007	<20	0.42	0.072	0.22	0.2	0.37	5.9	0.1	0.05	2	<0.5	<0.2
1162523	Rock	0.076	22	3	0.06	1457	0.010	<20	0.40	0.069	0.18	0.2	0.27	6.2	0.2	<0.05	2	<0.5	<0.2
1162524	Rock	0.068	20	5	0.05	2511	0.007	<20	0.34	0.092	0.14	0.3	0.81	5.8	0.2	0.06	2	<0.5	<0.2
1162525	Rock	0.048	23	5	0.18	3198	0.027	<20	0.45	0.064	0.31	0.6	0.45	4.7	0.2	0.10	3	<0.5	<0.2
1162526	Rock	0.037	40	7	0.22	506	0.038	<20	0.64	0.061	0.45	0.5	0.19	3.3	0.3	<0.05	4	<0.5	<0.2
1162527	Rock	0.038	33	6	0.21	1348	0.043	<20	0.53	0.088	0.36	0.8	0.22	3.6	0.2	0.12	3	<0.5	<0.2
1162528	Rock	0.051	19	6	0.32	866	0.009	<20	0.30	0.090	0.15	0.9	1.02	4.7	0.1	0.58	2	<0.5	<0.2
1162529	Rock	0.042	42	6	0.29	682	0.057	<20	0.76	0.067	0.53	0.6	1.41	3.4	0.3	0.10	4	<0.5	<0.2
1162530	Rock	0.040	39	6	0.27	686	0.054	<20	0.72	0.067	0.51	0.5	1.32	3.4	0.3	0.10	4	0.6	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 3 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162531	Rock	2.89	0.012	2.8	21.2	5.8	62	<0.1	5.1	7.8	657	2.91	15.8	<0.5	13.2	160	0.1	10.8	<0.1	30	2.03
1162532	Rock	2.77	<0.005	2.8	26.1	10.4	55	<0.1	3.7	7.2	635	2.78	236.3	2.5	10.5	132	<0.1	14.0	<0.1	20	1.61
1162533	Rock	2.63	0.011	2.5	18.9	11.8	72	<0.1	2.0	5.0	518	2.95	130.8	8.2	9.8	152	0.1	6.2	<0.1	25	1.53
1162534	Rock	3.04	0.013	1.4	5.1	9.6	66	<0.1	0.8	5.0	700	3.14	25.8	12.3	10.5	189	0.1	2.5	<0.1	20	2.01
1162535	Rock	2.96	<0.005	0.8	10.7	7.4	41	<0.1	1.3	4.6	584	2.55	10.9	4.2	11.0	149	<0.1	3.4	<0.1	16	1.60
1162536	Rock	2.98	<0.005	1.6	19.4	16.6	40	<0.1	9.7	9.4	749	2.69	52.3	1.0	5.8	217	<0.1	3.6	<0.1	19	2.52
1162537	Rock	2.76	<0.005	1.4	14.3	7.9	27	<0.1	2.5	4.1	466	1.90	15.6	2.0	12.3	152	<0.1	2.6	0.1	5	1.22
1162538	Rock	2.98	<0.005	2.8	11.3	5.0	34	<0.1	1.7	3.4	453	2.03	3.5	2.2	15.8	139	<0.1	3.5	<0.1	9	1.13
1162539	Rock	3.02	<0.005	1.4	5.7	5.8	31	<0.1	2.3	3.4	458	2.05	2.9	1.1	14.9	183	<0.1	1.5	<0.1	8	1.52
1162540	Rock Pulp	0.12	2.543	62.3	2267.7	1306.3	3739	27.0	191.0	19.9	640	5.48	1281.5	794.2	2.7	90	20.2	18.8	11.6	57	1.55
1162541	Rock	2.60	<0.005	2.1	11.7	6.6	38	<0.1	8.6	6.5	649	2.23	2.0	1.4	13.2	351	<0.1	3.3	<0.1	17	3.02
1162542	Rock	2.95	<0.005	2.2	16.0	6.0	47	<0.1	19.0	12.4	753	3.04	4.3	0.6	10.5	368	<0.1	4.9	<0.1	39	2.78
1162543	Rock	3.05	<0.005	2.6	6.8	6.8	35	<0.1	7.7	5.0	582	2.16	2.0	1.5	14.5	174	0.1	2.9	<0.1	20	2.13
1162544	Rock	3.26	<0.005	3.0	20.0	18.6	48	<0.1	1.6	4.3	601	2.73	2.8	2.1	13.3	184	<0.1	4.8	0.2	9	1.58
1162545	Rock	3.13	<0.005	2.2	8.4	9.7	36	<0.1	1.8	3.7	469	2.06	1.8	1.6	17.4	119	<0.1	1.0	0.1	14	1.01
1162546	Rock	2.80	<0.005	1.8	12.9	4.5	27	<0.1	1.9	2.9	363	1.80	1.7	1.1	16.8	82	<0.1	0.6	<0.1	11	0.86
1162547	Rock	2.99	<0.005	2.0	21.9	5.8	34	<0.1	1.8	3.4	422	2.02	1.5	2.5	16.4	190	<0.1	0.7	<0.1	13	1.12
1162548	Rock	3.01	<0.005	2.6	11.4	6.1	36	<0.1	2.0	3.7	417	2.04	1.7	0.9	17.2	165	<0.1	0.5	<0.1	13	1.12
1162549	Rock	2.96	<0.005	2.3	6.5	4.8	29	<0.1	7.8	3.0	385	1.77	1.5	1.1	15.5	1063	<0.1	0.4	<0.1	15	1.00
1162550	Rock	0.73	0.012	<0.1	1.3	1.1	13	<0.1	1.5	0.5	235	0.49	<0.5	<0.5	0.2	47	0.1	<0.1	<0.1	<2	19.64
1162551	Rock	3.04	0.051	1.3	5.9	5.6	31	<0.1	3.0	3.8	513	1.97	1.8	<0.5	15.7	404	<0.1	0.5	<0.1	12	1.71
1162552	Rock	2.79	<0.005	2.1	5.8	4.4	34	<0.1	1.5	2.8	397	1.83	1.7	2.3	17.4	140	<0.1	0.3	<0.1	9	0.69
1162553	Rock	3.31	<0.005	1.8	8.4	4.7	30	<0.1	2.3	3.2	465	1.91	1.9	1.1	16.1	314	<0.1	0.7	0.1	13	1.80
1162554	Rock	2.85	<0.005	2.0	7.2	4.1	43	<0.1	3.6	3.9	499	2.20	1.5	<0.5	13.7	142	<0.1	0.3	<0.1	18	1.28
1162555	Rock	3.39	0.023	1.8	6.9	4.1	38	<0.1	1.7	3.9	475	2.08	1.3	0.8	14.9	211	<0.1	0.3	<0.1	16	1.18
1162556	Rock	2.87	0.022	1.9	4.3	4.2	43	<0.1	1.4	5.0	627	2.49	1.6	0.8	12.6	>2000	<0.1	0.4	<0.1	24	1.70
1162557	Rock	3.26	<0.005	2.6	4.8	3.4	38	<0.1	1.8	3.7	526	2.35	1.2	<0.5	14.1	164	<0.1	0.1	<0.1	17	1.04
1162558	Rock	3.06	<0.005	2.4	7.7	4.3	37	<0.1	1.7	3.8	544	2.23	1.4	2.2	15.7	204	0.1	0.2	<0.1	15	1.19
1162559	Rock	3.02	<0.005	2.3	7.3	4.3	59	<0.1	2.3	5.8	849	3.01	1.8	1.3	15.2	500	<0.1	0.3	0.1	26	2.00
1162560	Rock	3.14	0.005	2.3	7.4	4.4	59	<0.1	2.1	5.6	822	3.03	1.4	<0.5	15.5	458	<0.1	0.4	0.1	25	1.95



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1162531	Rock	0.045	27	19	0.31	1029	0.021	<20	0.64	0.051	0.42	0.8	1.89	7.8	0.4	0.17	3	<0.5	<0.2
1162532	Rock	0.039	16	8	0.11	1034	0.001	<20	0.40	0.035	0.20	1.1	0.76	6.2	0.7	0.20	2	<0.5	<0.2
1162533	Rock	0.035	12	4	0.21	1633	<0.001	<20	0.43	0.035	0.19	1.2	0.60	5.8	0.2	0.21	1	<0.5	<0.2
1162534	Rock	0.061	15	4	0.38	1781	0.005	<20	0.49	0.037	0.27	0.5	0.23	4.8	0.2	0.28	2	<0.5	<0.2
1162535	Rock	0.037	15	5	0.42	751	0.005	<20	0.45	0.045	0.25	0.5	0.28	3.8	0.2	0.10	2	<0.5	<0.2
1162536	Rock	0.012	7	8	0.65	1714	<0.001	<20	0.44	0.007	0.29	0.5	1.00	6.1	0.3	0.22	1	<0.5	<0.2
1162537	Rock	0.022	16	5	0.30	999	0.001	<20	0.42	0.017	0.31	0.6	0.61	2.3	0.2	0.24	1	<0.5	<0.2
1162538	Rock	0.034	33	7	0.29	624	0.015	<20	0.48	0.048	0.33	1.3	0.31	2.9	0.1	0.21	2	<0.5	<0.2
1162539	Rock	0.032	29	7	0.46	566	0.006	<20	0.42	0.045	0.27	1.1	0.26	3.3	0.1	0.17	2	<0.5	<0.2
1162540	Rock Pulp	0.064	12	48	0.89	276	0.092	<20	1.56	0.085	0.20	9.3	0.78	4.5	1.3	1.55	6	4.3	0.8
1162541	Rock	0.032	20	9	0.90	1205	0.009	<20	0.41	0.043	0.27	0.9	0.34	4.1	0.1	0.11	2	<0.5	<0.2
1162542	Rock	0.079	19	17	0.97	972	0.021	<20	0.74	0.034	0.54	0.3	0.54	7.8	0.3	0.13	3	<0.5	<0.2
1162543	Rock	0.038	28	12	0.64	433	0.049	<20	0.87	0.034	0.68	0.6	0.27	4.0	0.3	0.13	4	<0.5	<0.2
1162544	Rock	0.052	25	8	0.49	1001	0.059	<20	0.88	0.040	0.66	0.7	0.40	4.1	0.3	0.23	5	<0.5	<0.2
1162545	Rock	0.036	42	9	0.43	772	0.066	<20	0.77	0.053	0.56	1.9	0.06	2.7	0.2	0.17	4	<0.5	<0.2
1162546	Rock	0.032	41	9	0.35	557	0.062	<20	0.72	0.069	0.50	2.6	0.02	2.3	0.2	0.21	4	<0.5	<0.2
1162547	Rock	0.036	46	8	0.35	578	0.049	<20	0.66	0.054	0.44	2.3	0.06	2.7	0.2	0.28	4	<0.5	<0.2
1162548	Rock	0.035	48	9	0.39	315	0.058	<20	0.73	0.062	0.51	2.3	0.02	2.7	0.2	0.19	5	<0.5	<0.2
1162549	Rock	0.034	42	20	0.33	492	0.067	<20	0.68	0.063	0.47	2.9	<0.01	2.0	0.2	0.17	4	<0.5	<0.2
1162550	Rock	0.016	<1	<1	12.35	19	<0.001	<20	0.03	0.001	0.02	<0.1	<0.01	1.8	<0.1	<0.05	<1	<0.5	<0.2
1162551	Rock	0.033	33	9	0.44	1638	0.036	<20	0.62	0.047	0.41	1.6	0.01	2.8	0.1	0.17	3	<0.5	<0.2
1162552	Rock	0.029	40	9	0.34	320	0.074	<20	0.76	0.073	0.47	3.2	0.01	1.6	0.2	0.14	4	<0.5	<0.2
1162553	Rock	0.035	39	9	0.35	626	0.050	<20	0.69	0.054	0.42	2.4	0.02	2.5	0.2	0.17	4	<0.5	<0.2
1162554	Rock	0.039	43	14	0.52	565	0.093	<20	0.96	0.072	0.63	2.9	0.03	2.9	0.3	0.17	5	<0.5	<0.2
1162555	Rock	0.045	43	9	0.45	250	0.088	<20	0.89	0.061	0.60	2.5	<0.01	2.1	0.3	0.16	5	<0.5	<0.2
1162556	Rock	0.061	43	8	0.60	473	0.088	<20	1.03	0.053	0.65	1.6	<0.01	2.8	0.2	0.26	6	0.6	<0.2
1162557	Rock	0.046	43	9	0.51	317	0.119	<20	1.06	0.061	0.71	2.2	0.03	2.4	0.3	0.16	6	<0.5	<0.2
1162558	Rock	0.043	44	8	0.45	409	0.093	<20	0.92	0.064	0.60	1.7	0.02	2.4	0.2	0.17	5	0.5	<0.2
1162559	Rock	0.052	45	10	0.95	375	0.129	<20	1.50	0.049	1.16	1.1	0.02	3.3	0.4	0.34	7	<0.5	<0.2
1162560	Rock	0.051	47	10	0.90	366	0.127	<20	1.44	0.051	1.13	1.1	0.03	3.3	0.4	0.33	7	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 4 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162561	Rock	3.34	0.007	2.3	6.7	4.0	35	<0.1	1.7	3.6	462	2.19	1.6	<0.5	17.2	314	<0.1	0.3	<0.1	15	1.19
1162562	Rock	3.15	<0.005	2.0	11.9	5.6	35	<0.1	1.2	3.6	540	2.28	1.3	1.3	15.6	169	<0.1	0.7	<0.1	15	1.58
1162563	Rock	3.00	<0.005	1.9	14.5	3.9	37	<0.1	1.7	4.2	482	2.45	3.4	0.8	15.1	71	<0.1	0.4	<0.1	14	1.02
1162564	Rock	2.81	0.011	2.6	27.5	3.9	37	<0.1	1.2	4.5	415	2.53	2.2	<0.5	14.0	97	<0.1	0.3	<0.1	14	0.78
1162565	Rock	3.05	<0.005	2.9	32.3	3.6	40	<0.1	1.4	5.1	475	2.82	2.8	<0.5	12.8	522	<0.1	0.3	<0.1	14	1.21
1162566	Rock	2.98	0.011	2.2	28.0	4.9	38	<0.1	1.3	4.4	462	2.72	8.5	<0.5	14.4	161	<0.1	0.7	<0.1	12	1.01
1162567	Rock	2.51	<0.005	2.9	22.9	8.1	33	<0.1	1.3	4.7	536	2.58	2.4	<0.5	13.7	>2000	<0.1	1.3	<0.1	11	2.14
1162568	Rock	2.63	<0.005	2.0	21.7	8.0	44	<0.1	1.3	4.7	477	2.79	2.6	0.9	16.8	283	<0.1	1.8	<0.1	12	1.38
1162569	Rock	1.80	<0.005	2.4	18.6	6.6	41	<0.1	1.5	4.3	502	2.48	1.3	3.0	13.8	254	<0.1	1.0	<0.1	17	1.50
1162570	Rock Pulp	0.13	0.850	4.5	32.6	5.5	49	0.3	24.0	9.1	399	2.58	6.5	1188.7	1.0	42	0.1	1.0	0.2	59	0.85



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000268.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1162561	Rock	0.037	49	10	0.47	259	0.092	<20	0.90	0.072	0.61	2.4	0.02	2.7	0.2	0.22	5	<0.5	<0.2
1162562	Rock	0.036	36	9	0.44	656	0.044	<20	0.68	0.046	0.46	1.8	0.03	3.3	0.2	0.21	4	<0.5	<0.2
1162563	Rock	0.039	45	10	0.48	252	0.101	<20	0.94	0.074	0.64	2.6	0.05	2.4	0.3	0.26	6	0.7	<0.2
1162564	Rock	0.048	44	9	0.45	265	0.117	<20	1.03	0.068	0.61	3.3	0.04	1.6	0.3	0.37	6	<0.5	<0.2
1162565	Rock	0.054	43	9	0.52	349	0.127	<20	1.09	0.074	0.68	3.4	0.05	2.3	0.3	0.47	7	<0.5	<0.2
1162566	Rock	0.048	47	8	0.47	493	0.098	<20	1.00	0.061	0.60	2.6	0.08	2.5	0.2	0.37	6	<0.5	<0.2
1162567	Rock	0.047	42	9	0.37	1741	0.021	<20	0.58	0.050	0.30	1.9	0.18	2.7	0.1	0.32	3	<0.5	0.6
1162568	Rock	0.054	50	10	0.43	510	0.020	<20	0.69	0.048	0.33	1.3	0.20	3.1	0.1	0.26	4	<0.5	<0.2
1162569	Rock	0.048	40	11	0.46	662	0.068	<20	0.88	0.060	0.51	2.2	0.07	2.4	0.2	0.22	5	<0.5	<0.2
1162570	Rock Pulp	0.056	4	32	0.74	94	0.126	<20	1.54	0.086	0.14	11.6	0.06	4.9	<0.1	<0.05	5	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000268.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1162523	Rock	2.59	0.006	1.0	9.1	25.6	98	<0.1	1.4	4.3	835	3.09	6.0	3.8	15.3	56	0.3	3.1	0.1	53	0.22
REP 1162523	QC		<0.005	1.1	9.4	25.1	95	<0.1	1.4	4.6	831	3.08	6.2	2.6	14.9	54	0.3	3.1	0.1	54	0.22
1162557	Rock	3.26	<0.005	2.6	4.8	3.4	38	<0.1	1.8	3.7	526	2.35	1.2	<0.5	14.1	164	<0.1	0.1	<0.1	17	1.04
REP 1162557	QC			3.1	5.1	3.4	40	<0.1	1.5	4.1	542	2.38	0.8	<0.5	14.8	167	<0.1	0.1	<0.1	17	1.06
1162558	Rock	3.06	<0.005	2.4	7.7	4.3	37	<0.1	1.7	3.8	544	2.23	1.4	2.2	15.7	204	0.1	0.2	<0.1	15	1.19
REP 1162558	QC		0.008																		
1162570	Rock Pulp	0.13	0.850	4.5	32.6	5.5	49	0.3	24.0	9.1	399	2.58	6.5	1188.7	1.0	42	0.1	1.0	0.2	59	0.85
REP 1162570	QC			3.8	31.3	5.6	52	0.3	24.5	8.8	397	2.56	6.9	1249.8	0.9	42	0.2	1.0	0.1	59	0.84
Core Reject Duplicates																					
1162526	Rock	3.16	<0.005	1.9	5.6	6.0	42	<0.1	1.8	3.4	469	2.16	3.6	<0.5	18.0	64	<0.1	2.7	<0.1	14	1.06
DUP 1162526	QC		<0.005	1.4	5.5	5.9	41	<0.1	1.7	3.2	457	2.05	3.6	<0.5	17.2	59	<0.1	2.7	<0.1	13	1.01
1162560	Rock	3.14	0.005	2.3	7.4	4.4	59	<0.1	2.1	5.6	822	3.03	1.4	<0.5	15.5	458	<0.1	0.4	0.1	25	1.95
DUP 1162560	QC		<0.005	2.5	7.6	4.4	59	<0.1	2.1	5.2	834	2.99	1.1	1.5	15.6	475	<0.1	0.3	0.1	25	1.98
Reference Materials																					
STD DS10	Standard			13.7	149.6	144.8	362	2.0	74.2	12.6	873	2.81	43.9	68.7	7.4	72	2.4	8.8	12.8	42	1.07
STD DS10	Standard			15.4	158.7	160.1	370	2.0	76.7	13.4	903	2.85	45.5	59.2	7.6	75	2.3	8.8	13.8	43	1.11
STD DS10	Standard			15.5	152.8	148.0	374	2.0	74.6	13.0	892	2.79	44.1	74.4	7.4	74	2.5	8.2	13.2	43	1.08
STD OREAS45EA	Standard			2.0	730.1	14.7	33	0.3	401.5	54.5	441	24.22	11.9	50.3	10.6	4	<0.1	0.4	0.3	325	0.03
STD OREAS45EA	Standard			1.6	730.6	14.9	33	0.3	429.8	55.3	426	24.36	12.4	53.2	10.8	4	<0.1	0.4	0.3	326	0.03
STD OREAS45EA	Standard			1.8	718.4	14.7	32	0.3	423.8	56.1	419	23.34	11.6	80.8	10.6	4	<0.1	0.4	0.3	318	0.03
STD OXD108	Standard		0.427																		
STD OXD108	Standard		0.397																		
STD OXI121	Standard		1.914																		
STD OXI121	Standard		1.747																		
STD OXN117	Standard		7.950																		
STD OXN117	Standard		7.723																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000268.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1162523	Rock	0.076	22	3	0.06	1457	0.010	<20	0.40	0.069	0.18	0.2	0.27	6.2	0.2	<0.05	2	<0.5	<0.2
REP 1162523	QC	0.073	21	3	0.06	1463	0.010	<20	0.40	0.068	0.18	0.3	0.33	6.0	0.1	<0.05	2	<0.5	<0.2
1162557	Rock	0.046	43	9	0.51	317	0.119	<20	1.06	0.061	0.71	2.2	0.03	2.4	0.3	0.16	6	<0.5	<0.2
REP 1162557	QC	0.047	44	9	0.52	327	0.124	<20	1.07	0.061	0.73	2.3	0.01	2.3	0.3	0.17	7	<0.5	<0.2
1162558	Rock	0.043	44	8	0.45	409	0.093	<20	0.92	0.064	0.60	1.7	0.02	2.4	0.2	0.17	5	0.5	<0.2
REP 1162558	QC																		
1162570	Rock Pulp	0.056	4	32	0.74	94	0.126	<20	1.54	0.086	0.14	11.6	0.06	4.9	<0.1	<0.05	5	<0.5	<0.2
REP 1162570	QC	0.054	5	31	0.73	94	0.127	<20	1.53	0.086	0.13	11.8	0.06	4.7	<0.1	<0.05	5	<0.5	<0.2
Core Reject Duplicates																			
1162526	Rock	0.037	40	7	0.22	506	0.038	<20	0.64	0.061	0.45	0.5	0.19	3.3	0.3	<0.05	4	<0.5	<0.2
DUP 1162526	QC	0.033	40	7	0.22	487	0.036	<20	0.60	0.053	0.43	0.6	0.19	3.1	0.2	<0.05	4	<0.5	<0.2
1162560	Rock	0.051	47	10	0.90	366	0.127	<20	1.44	0.051	1.13	1.1	0.03	3.3	0.4	0.33	7	<0.5	<0.2
DUP 1162560	QC	0.049	44	10	0.91	353	0.126	<20	1.45	0.046	1.13	1.2	0.01	3.1	0.4	0.33	7	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.076	17	54	0.77	422	0.080	<20	1.04	0.067	0.33	2.8	0.30	3.1	4.7	0.27	4	3.2	4.7
STD DS10	Standard	0.083	18	57	0.80	436	0.080	<20	1.07	0.072	0.35	3.0	0.35	2.9	5.3	0.30	4	2.4	4.9
STD DS10	Standard	0.074	18	57	0.80	428	0.081	<20	1.08	0.072	0.34	2.7	0.28	3.0	4.8	0.29	4	3.1	5.3
STD OREAS45EA	Standard	0.030	7	892	0.11	148	0.098	<20	3.31	0.018	0.05	<0.1	0.02	84.8	<0.1	<0.05	13	2.5	<0.2
STD OREAS45EA	Standard	0.032	7	899	0.11	153	0.102	<20	3.58	0.023	0.06	<0.1	0.02	85.7	<0.1	<0.05	12	1.3	<0.2
STD OREAS45EA	Standard	0.029	7	887	0.11	144	0.099	<20	3.59	0.022	0.06	<0.1	<0.01	80.1	<0.1	<0.05	12	1.6	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000268.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OXD108 Expected		0.414																			
STD OXN117 Expected		7.679																			
STD OXI121 Expected		1.834																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank	<0.005																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.7	3.6	9.9	44	<0.1	0.8	3.5	423	1.80	0.8	1.7	2.4	29	0.1	<0.1	<0.1	23	0.64	
ROCK-WHI	Prep Blank	<0.005	1.6	3.6	15.2	40	<0.1	0.7	3.5	436	1.81	0.8	1.4	2.5	25	<0.1	<0.1	<0.1	23	0.63	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: September 22, 2016

Page: 2 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000268.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.038	5	3	0.39	74	0.090	<20	0.92	0.097	0.09	0.2	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.041	6	2	0.41	63	0.085	<20	0.95	0.099	0.09	0.1	<0.01	3.1	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 19, 2016
Report Date: October 06, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000284.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-09-Rock-RAB
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162609	Rock	1.68	0.024	2.9	41.3	12.9	49	<0.1	10.7	14.5	927	3.27	39.1	20.0	6.7	74	0.1	2.2	0.2	67	0.14
1162620	Rock	0.63	<0.005	<0.1	2.1	1.3	15	<0.1	1.5	0.7	214	0.41	<0.5	<0.5	<0.1	50	<0.1	<0.1	<0.1	<2	19.79
1162621	Rock	2.35	0.008	0.5	85.9	1.3	58	<0.1	14.4	17.4	529	3.63	1.5	3.6	1.6	84	0.1	0.4	<0.1	112	1.68
1162622	Rock	2.44	0.006	0.7	88.2	3.5	62	<0.1	29.4	22.1	551	4.15	2.1	2.4	1.7	144	0.1	1.5	<0.1	136	2.31
1162623	Rock	3.39	<0.005	0.4	21.1	2.1	75	<0.1	30.7	20.8	961	4.35	1.3	1.5	1.5	158	<0.1	0.7	<0.1	132	3.54
1162624	Rock	2.49	<0.005	0.8	40.4	2.4	53	<0.1	8.2	12.9	600	3.30	8.4	<0.5	1.7	142	<0.1	1.3	<0.1	57	3.38
1162625	Rock	3.33	<0.005	0.5	58.1	1.8	67	<0.1	7.1	14.4	439	3.68	3.7	1.0	1.9	129	<0.1	1.8	<0.1	61	2.71
1162626	Rock	3.08	<0.005	1.4	18.1	6.0	76	<0.1	8.5	21.3	747	4.70	24.3	1.3	1.7	278	<0.1	1.3	<0.1	73	8.23
1162627	Rock	2.33	<0.005	0.6	25.1	2.6	65	<0.1	14.9	22.0	786	4.64	10.1	<0.5	1.5	213	<0.1	1.5	<0.1	122	4.39
1162628	Rock	2.66	0.006	0.9	28.8	3.6	73	<0.1	17.7	21.5	690	4.30	6.0	1.6	1.8	224	0.2	1.1	<0.1	92	3.64
1162629	Rock	3.23	<0.005	1.0	5.3	4.6	70	<0.1	8.4	15.4	746	3.51	19.7	1.8	1.2	144	<0.1	2.0	<0.1	74	3.03
1162640	Rock Pulp	0.12	2.162	60.7	2138.6	1230.4	3613	25.8	176.3	19.1	601	4.94	1126.1	1484.0	2.9	78	23.5	18.7	10.9	54	1.42
1162641	Rock	3.30	<0.005	0.7	124.1	1.5	62	<0.1	9.7	20.4	712	4.14	1.6	1.0	0.7	73	<0.1	0.1	<0.1	143	1.48
1162642	Rock	3.40	0.037	1.1	330.4	1.2	68	<0.1	4.6	16.3	845	3.74	2.6	2.5	0.5	89	0.3	0.1	<0.1	141	1.85
1162643	Rock	2.30	<0.005	1.7	125.4	1.8	41	<0.1	13.6	18.4	628	3.17	2.4	1.9	0.5	75	0.1	0.2	<0.1	117	1.80
1162644	Rock	3.01	<0.005	2.0	65.3	1.9	37	<0.1	9.1	12.6	498	2.73	3.9	0.6	0.6	98	<0.1	0.1	<0.1	95	1.58
1162645	Rock	1.93	0.010	1.3	84.5	1.7	60	<0.1	11.0	18.3	718	3.96	2.3	13.5	0.8	60	<0.1	0.1	<0.1	123	1.31
1162646	Rock	3.01	0.010	8.1	73.7	1.9	58	<0.1	19.5	17.7	702	4.08	2.3	5.6	2.0	66	0.1	0.2	<0.1	131	1.36
1162647	Rock	2.56	0.005	2.0	61.9	3.6	54	<0.1	8.4	15.5	773	3.48	1.6	3.4	6.9	64	<0.1	0.1	<0.1	100	1.51
1162648	Rock	2.82	0.013	3.4	23.9	7.3	40	<0.1	7.7	6.8	506	2.11	5.9	9.5	5.2	78	<0.1	0.3	<0.1	51	1.19
1162649	Rock	2.46	0.014	1.6	29.8	2.8	54	<0.1	26.5	17.9	790	3.88	6.6	11.2	1.9	151	<0.1	0.3	<0.1	111	2.73
1162610	Rock Pulp	0.12	0.835	3.9	33.3	5.8	50	0.2	23.1	9.1	394	2.51	6.4	580.1	1.0	41	0.2	1.0	0.1	59	0.78
1162611	Rock	2.46	<0.005	0.8	31.6	1.3	95	<0.1	4.7	11.0	768	3.56	8.6	0.7	0.7	25	0.1	0.5	<0.1	81	0.50
1162612	Rock	3.82	0.010	0.7	36.7	2.0	60	<0.1	3.7	11.3	916	3.72	3.8	3.8	1.0	34	0.1	0.9	<0.1	80	0.35
1162613	Rock	4.85	0.018	0.6	40.2	2.4	67	<0.1	9.2	16.0	1279	3.97	2.2	19.8	0.9	29	0.4	0.2	<0.1	114	0.39
1162614	Rock	3.52	<0.005	1.0	39.7	1.4	72	<0.1	13.1	15.8	642	3.68	1.6	1.7	0.5	36	<0.1	0.1	<0.1	100	0.54
1162615	Rock	2.52	0.007	0.9	55.3	3.7	62	<0.1	8.6	19.4	582	3.57	3.3	4.0	0.6	90	0.1	0.3	0.1	87	0.51
1162616	Rock	2.36	<0.005	0.7	54.6	3.4	67	<0.1	8.5	14.5	620	3.51	3.2	2.1	0.8	49	0.1	0.7	<0.1	95	0.52
1162617	Rock	2.79	<0.005	0.5	82.3	1.3	64	<0.1	16.7	21.2	600	4.35	2.4	1.3	0.4	57	<0.1	0.3	<0.1	162	0.57
1162618	Rock	2.09	<0.005	0.7	9.8	6.2	57	<0.1	15.1	15.0	590	3.08	3.4	<0.5	0.4	79	0.1	0.6	<0.1	99	0.66



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1162609	Rock	0.038	11	17	0.26	1058	0.007	<20	0.72	0.022	0.42	0.5	0.34	14.5	0.3	<0.05	2	<0.5	<0.2	
1162620	Rock	0.015	<1	<1	12.26	18	<0.001	<20	0.03	<0.001	0.02	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2	
1162621	Rock	0.084	8	28	1.24	407	0.138	<20	1.66	0.078	0.72	0.1	0.03	12.5	0.1	<0.05	7	<0.5	<0.2	
1162622	Rock	0.055	8	27	1.34	431	0.111	<20	1.91	0.030	0.84	0.1	0.21	16.3	0.2	<0.05	7	0.7	<0.2	
1162623	Rock	0.051	8	103	2.19	428	0.175	<20	2.41	0.036	1.45	<0.1	0.04	17.7	0.3	<0.05	9	<0.5	<0.2	
1162624	Rock	0.070	8	22	0.48	663	0.019	<20	0.75	0.029	0.31	0.4	0.30	13.5	0.1	<0.05	3	<0.5	<0.2	
1162625	Rock	0.071	7	13	0.62	443	0.021	<20	0.96	0.032	0.36	0.2	0.18	14.4	<0.1	<0.05	4	<0.5	<0.2	
1162626	Rock	0.058	9	10	0.72	194	0.013	<20	1.10	0.008	0.43	0.2	0.78	12.7	0.1	<0.05	3	<0.5	<0.2	
1162627	Rock	0.058	9	74	1.31	175	0.037	<20	1.83	0.028	0.37	0.1	0.36	20.6	<0.1	<0.05	7	<0.5	<0.2	
1162628	Rock	0.074	11	66	1.38	222	0.043	<20	1.64	0.015	0.72	0.2	0.13	21.2	0.1	<0.05	5	<0.5	<0.2	
1162629	Rock	0.097	7	26	0.78	219	0.071	<20	1.12	0.052	0.39	0.4	0.93	11.3	0.2	<0.05	4	<0.5	<0.2	
1162640	Rock Pulp	0.058	12	43	0.83	249	0.090	<20	1.44	0.077	0.19	9.4	0.75	4.1	1.3	1.44	6	3.6	0.5	
1162641	Rock	0.048	3	14	1.68	316	0.194	<20	2.03	0.114	1.07	0.4	0.03	9.9	0.2	<0.05	7	<0.5	<0.2	
1162642	Rock	0.058	3	11	1.21	316	0.168	<20	1.32	0.133	0.57	0.5	0.05	9.4	0.1	<0.05	7	<0.5	<0.2	
1162643	Rock	0.051	2	42	1.18	255	0.179	<20	1.25	0.119	0.55	0.3	0.04	9.1	0.2	<0.05	5	<0.5	<0.2	
1162644	Rock	0.059	3	26	0.97	698	0.162	<20	1.13	0.129	0.47	0.6	0.03	7.4	0.1	<0.05	5	<0.5	<0.2	
1162645	Rock	0.059	5	37	1.65	304	0.191	<20	1.91	0.085	0.96	0.3	0.04	10.8	0.2	<0.05	8	<0.5	<0.2	
1162646	Rock	0.054	6	61	1.77	380	0.204	<20	1.92	0.082	1.17	0.3	0.04	12.3	0.3	<0.05	7	<0.5	<0.2	
1162647	Rock	0.066	15	22	1.51	380	0.159	<20	1.74	0.059	1.07	0.4	0.02	9.7	0.3	0.05	7	<0.5	<0.2	
1162648	Rock	0.040	11	27	0.55	198	0.069	<20	0.77	0.047	0.49	0.9	0.09	5.5	0.2	<0.05	4	<0.5	<0.2	
1162649	Rock	0.057	7	80	1.60	281	0.133	<20	1.72	0.058	1.14	0.4	0.04	12.9	0.3	<0.05	7	<0.5	<0.2	
1162610	Rock Pulp	0.054	5	31	0.71	98	0.133	<20	1.43	0.078	0.13	10.9	0.04	4.8	<0.1	<0.05	5	<0.5	<0.2	
1162611	Rock	0.082	4	13	0.77	480	0.141	<20	1.25	0.047	0.69	0.4	0.14	10.4	0.1	<0.05	6	<0.5	<0.2	
1162612	Rock	0.090	7	9	0.49	671	0.073	<20	0.80	0.060	0.38	0.4	0.11	14.2	<0.1	<0.05	5	<0.5	<0.2	
1162613	Rock	0.059	6	29	1.29	465	0.167	<20	1.59	0.060	0.82	0.3	0.04	14.5	0.2	<0.05	6	<0.5	<0.2	
1162614	Rock	0.071	3	44	1.71	448	0.228	<20	2.02	0.058	1.20	0.5	0.01	8.5	0.2	<0.05	7	<0.5	<0.2	
1162615	Rock	0.063	3	17	1.17	567	0.173	<20	1.34	0.069	0.61	0.5	0.03	7.0	0.1	<0.05	6	<0.5	<0.2	
1162616	Rock	0.068	5	18	1.21	547	0.153	<20	1.59	0.061	0.75	0.4	0.03	11.6	0.1	<0.05	6	<0.5	<0.2	
1162617	Rock	0.064	3	34	1.98	422	0.192	<20	2.18	0.069	1.11	0.2	0.02	13.8	0.3	<0.05	7	<0.5	<0.2	
1162618	Rock	0.052	3	82	1.36	592	0.147	<20	1.43	0.074	0.42	0.5	0.05	12.0	0.1	<0.05	6	<0.5	<0.2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162619	Rock	3.01	<0.005	0.6	20.6	2.4	33	<0.1	9.5	9.9	390	1.96	1.7	<0.5	0.6	92	<0.1	0.2	<0.1	65	0.74
1162581	Rock	3.85	<0.005	1.2	5.9	6.2	25	<0.1	1.2	3.6	758	2.18	9.1	0.6	11.5	692	<0.1	0.8	<0.1	23	2.22
1162582	Rock	4.04	<0.005	1.7	11.5	5.9	37	<0.1	1.3	4.6	641	2.37	4.3	<0.5	10.9	307	<0.1	0.8	<0.1	16	1.62
1162583	Rock	3.72	<0.005	2.3	7.1	4.6	50	<0.1	1.5	4.4	681	2.63	2.1	0.7	10.5	141	<0.1	0.5	<0.1	17	1.46
1162584	Rock	3.93	<0.005	2.2	11.6	4.7	42	<0.1	1.8	5.3	624	2.42	4.3	<0.5	13.6	141	<0.1	0.5	<0.1	14	1.33
1162585	Rock	3.77	<0.005	1.9	15.1	6.5	35	<0.1	3.0	4.0	478	1.97	3.9	1.5	14.4	80	<0.1	1.5	<0.1	13	1.09
1162586	Rock	3.92	0.005	1.7	10.8	9.5	39	<0.1	3.2	4.9	716	2.42	7.5	1.6	11.6	126	0.2	1.3	<0.1	27	2.01
1162587	Rock	3.20	0.012	1.8	13.9	6.7	21	<0.1	2.0	2.9	582	2.20	18.7	16.2	12.4	107	0.1	1.4	<0.1	23	1.27
1162588	Rock	3.08	0.015	3.0	15.0	5.4	29	<0.1	2.2	3.3	459	1.83	4.9	5.2	14.6	76	<0.1	1.5	<0.1	8	1.39
1162630	Rock	3.49	<0.005	1.0	5.3	4.3	71	<0.1	9.4	15.8	786	3.66	19.0	1.2	1.2	144	<0.1	1.7	<0.1	76	3.21
1162631	Rock	3.52	<0.005	1.0	22.3	4.1	61	<0.1	6.7	16.1	807	4.05	10.9	<0.5	1.5	169	<0.1	2.0	<0.1	92	3.17
1162632	Rock	2.61	<0.005	0.9	38.0	2.4	67	<0.1	7.0	15.4	733	3.87	14.4	1.2	1.5	160	<0.1	1.3	<0.1	102	3.12
1162633	Rock	3.25	<0.005	0.8	15.7	4.8	59	<0.1	6.1	12.5	728	2.95	3.2	<0.5	1.2	532	0.1	1.3	<0.1	81	4.63
1162634	Rock	2.80	<0.005	1.5	14.4	2.2	66	<0.1	7.0	14.8	809	4.05	9.6	<0.5	1.6	155	<0.1	0.7	<0.1	114	3.01
1162635	Rock	3.62	<0.005	1.1	17.7	4.5	65	<0.1	9.6	19.4	814	4.52	36.7	0.7	1.6	219	0.1	2.7	<0.1	116	4.31
1162636	Rock	2.66	0.093	0.7	13.5	2.3	76	0.2	30.0	20.6	847	4.86	4.5	430.6	1.6	211	<0.1	1.0	<0.1	127	3.89
1162637	Rock	3.62	0.008	0.8	26.4	1.1	58	<0.1	10.3	15.6	518	3.52	1.9	5.5	1.1	61	<0.1	0.2	<0.1	100	1.18
1162638	Rock	3.00	<0.005	0.9	81.8	1.4	53	<0.1	16.6	15.7	569	3.28	1.1	1.2	0.9	57	<0.1	0.1	<0.1	106	1.47
1162639	Rock	3.91	<0.005	0.6	39.1	1.5	55	<0.1	12.5	15.2	511	3.26	1.2	1.0	0.9	58	<0.1	<0.1	<0.1	107	1.47
1162589	Rock	2.76	<0.005	1.1	64.0	1.7	110	<0.1	10.8	15.3	938	3.95	51.0	<0.5	1.1	46	0.2	2.2	<0.1	90	0.71
1162590	Rock	3.66	<0.005	1.0	66.7	1.6	127	<0.1	9.0	14.3	1024	3.99	48.2	<0.5	1.2	43	0.2	1.9	<0.1	90	0.68
1162591	Rock	3.42	0.005	1.0	35.6	1.1	118	<0.1	3.4	11.1	886	3.80	17.4	2.2	0.9	32	0.2	0.4	<0.1	79	0.47
1162592	Rock	4.43	<0.005	1.5	13.9	1.4	69	<0.1	5.2	9.8	1228	3.74	36.2	1.6	0.9	27	0.2	1.0	<0.1	98	0.34
1162593	Rock	2.72	0.006	1.4	30.3	1.8	80	<0.1	4.1	12.8	1257	4.20	65.3	3.7	0.9	35	0.2	2.1	<0.1	118	0.33
1162594	Rock	1.58	<0.005	0.8	73.9	1.1	71	<0.1	5.3	12.5	866	3.74	22.2	34.6	1.0	40	<0.1	1.8	<0.1	83	0.53
1162595	Rock	1.69	0.005	1.9	83.3	6.3	95	<0.1	13.8	17.0	1178	4.56	94.9	10.2	0.8	178	0.2	3.6	<0.1	143	0.16
1162596	Rock	2.13	<0.005	6.2	45.4	24.4	79	<0.1	20.9	11.9	862	3.75	91.9	2.1	0.6	76	0.1	3.5	0.1	107	0.18
1162597	Rock	3.31	<0.005	1.9	14.3	115.4	26	<0.1	7.6	3.2	265	1.50	46.0	5.8	0.2	65	0.1	3.1	1.2	44	0.05
1162598	Rock	2.20	0.008	3.7	30.3	155.1	103	<0.1	9.5	13.9	780	4.84	153.1	8.0	0.8	54	0.3	7.7	0.7	170	0.09
1162599	Rock	2.98	0.010	2.8	56.0	7.8	95	<0.1	9.6	20.4	1003	4.57	98.0	10.1	1.2	58	0.2	6.0	<0.1	127	0.13



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1162619	Rock	0.052	3	56	0.85	623	0.147	<20	0.84	0.087	0.25	0.4	0.03	6.9	<0.1	<0.05	3	<0.5	<0.2
1162581	Rock	0.046	25	4	0.60	1257	0.018	<20	0.22	0.065	0.13	0.6	1.02	3.6	<0.1	0.27	1	<0.5	<0.2
1162582	Rock	0.050	33	5	0.48	885	0.071	<20	0.60	0.051	0.45	0.8	0.43	3.1	0.2	0.27	3	<0.5	<0.2
1162583	Rock	0.056	34	5	0.53	599	0.114	<20	0.97	0.053	0.70	0.8	0.15	3.8	0.2	0.13	5	<0.5	<0.2
1162584	Rock	0.045	38	6	0.46	507	0.094	<20	0.89	0.047	0.62	0.8	0.16	3.4	0.3	0.32	5	<0.5	<0.2
1162585	Rock	0.030	33	9	0.36	323	0.043	<20	0.60	0.056	0.39	0.9	0.36	3.1	0.2	0.21	3	<0.5	<0.2
1162586	Rock	0.055	22	8	0.58	529	0.015	<20	0.39	0.051	0.27	0.4	1.00	5.6	0.1	0.23	2	<0.5	<0.2
1162587	Rock	0.035	22	5	0.39	899	0.005	<20	0.24	0.083	0.14	0.5	2.49	3.8	<0.1	0.46	1	<0.5	<0.2
1162588	Rock	0.033	34	6	0.29	361	0.008	<20	0.32	0.049	0.22	0.4	0.57	3.1	<0.1	0.25	2	<0.5	<0.2
1162630	Rock	0.103	7	28	0.81	231	0.077	<20	1.19	0.064	0.42	0.4	0.80	12.4	0.2	<0.05	5	<0.5	<0.2
1162631	Rock	0.088	9	11	0.45	716	0.032	<20	0.78	0.055	0.31	0.4	0.28	14.0	0.1	<0.05	4	<0.5	<0.2
1162632	Rock	0.076	8	21	0.93	282	0.114	<20	1.44	0.093	0.52	0.3	0.23	13.2	0.1	<0.05	6	<0.5	<0.2
1162633	Rock	0.065	8	25	0.97	1410	0.140	<20	1.21	0.079	0.57	0.6	0.09	10.2	0.1	<0.05	5	<0.5	<0.2
1162634	Rock	0.070	9	33	1.26	338	0.145	<20	1.66	0.072	0.88	0.3	0.14	13.4	0.2	<0.05	7	<0.5	<0.2
1162635	Rock	0.082	10	13	0.78	999	0.016	<20	1.38	0.037	0.24	0.2	1.73	17.8	<0.1	<0.05	5	<0.5	<0.2
1162636	Rock	0.068	11	89	1.70	510	0.082	<20	2.40	0.030	0.84	0.2	0.27	18.4	0.2	<0.05	9	<0.5	<0.2
1162637	Rock	0.057	5	48	1.89	369	0.218	<20	2.23	0.072	1.32	0.3	0.05	9.1	0.2	<0.05	7	<0.5	<0.2
1162638	Rock	0.065	4	59	1.47	290	0.220	<20	1.68	0.142	0.71	0.3	0.03	8.3	0.1	<0.05	6	<0.5	<0.2
1162639	Rock	0.057	4	42	1.63	213	0.187	<20	1.80	0.126	0.79	0.3	0.02	8.9	0.2	<0.05	7	<0.5	<0.2
1162589	Rock	0.075	6	37	0.80	511	0.069	<20	1.26	0.057	0.51	0.5	0.63	15.0	0.3	<0.05	5	<0.5	<0.2
1162590	Rock	0.084	6	32	0.77	481	0.067	<20	1.27	0.069	0.49	0.5	0.59	15.1	0.3	<0.05	6	<0.5	<0.2
1162591	Rock	0.092	6	9	0.91	1286	0.146	<20	1.53	0.060	0.91	0.4	0.21	11.2	0.2	<0.05	6	<0.5	<0.2
1162592	Rock	0.087	6	9	0.25	335	0.056	<20	0.59	0.089	0.30	1.2	0.50	14.8	0.1	<0.05	3	<0.5	<0.2
1162593	Rock	0.093	5	9	0.21	643	0.021	<20	0.62	0.054	0.32	24.8	0.95	17.3	0.4	<0.05	3	<0.5	<0.2
1162594	Rock	0.095	7	18	0.53	506	0.087	<20	0.95	0.097	0.48	0.6	0.32	14.9	0.2	<0.05	5	<0.5	<0.2
1162595	Rock	0.035	4	16	0.12	4257	0.006	<20	0.56	0.019	0.15	0.7	0.94	17.8	0.3	0.12	2	<0.5	<0.2
1162596	Rock	0.027	3	38	0.14	1771	0.012	<20	0.60	0.022	0.15	1.1	0.81	13.2	0.4	<0.05	2	<0.5	<0.2
1162597	Rock	0.005	<1	12	0.06	3010	0.005	<20	0.19	0.004	0.03	1.6	0.56	2.9	0.4	0.08	<1	<0.5	<0.2
1162598	Rock	0.013	2	29	0.10	427	0.002	<20	0.70	0.003	0.10	1.5	1.32	16.5	1.2	<0.05	2	<0.5	<0.2
1162599	Rock	0.022	3	18	0.15	313	0.001	<20	0.69	0.015	0.23	0.4	1.29	26.6	1.0	<0.05	2	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162600	Rock Pulp	0.13	2.064	64.1	2155.6	1352.1	3563	25.0	185.5	19.8	614	5.16	1170.6	1019.6	2.7	81	22.7	18.3	10.6	55	1.46
1162601	Rock	1.39	0.009	4.5	32.5	11.2	112	<0.1	13.0	27.8	1322	7.24	193.0	8.8	0.9	104	0.3	5.5	<0.1	152	0.16
1162602	Rock	1.52	0.005	6.5	26.0	8.7	98	<0.1	13.9	24.4	1586	6.53	132.4	7.2	1.0	100	0.2	4.1	<0.1	144	0.17
1162603	Rock	1.69	0.008	7.7	64.5	10.7	88	<0.1	13.8	24.2	1365	6.79	141.7	7.8	0.8	91	0.2	8.5	<0.1	162	0.18
1162604	Rock	1.53	0.007	5.9	124.2	7.1	80	<0.1	11.3	27.8	1378	6.95	101.4	8.1	0.7	76	0.2	9.7	<0.1	172	0.23
1162605	Rock	1.33	0.006	9.6	93.8	5.8	88	<0.1	19.8	27.8	1653	6.95	116.1	5.2	1.0	148	0.3	5.6	<0.1	181	0.22
1162606	Rock	1.79	0.007	4.7	41.1	3.7	87	<0.1	9.2	21.4	1480	5.83	82.9	8.5	1.0	92	0.2	4.0	<0.1	156	0.20
1162607	Rock	1.71	0.006	3.3	51.1	5.0	86	<0.1	13.7	21.0	994	5.21	59.2	6.7	2.7	92	0.2	3.3	0.1	136	0.21
1162608	Rock	2.04	0.011	3.2	58.5	5.8	72	<0.1	10.6	20.5	1210	4.98	40.7	10.0	4.8	70	<0.1	3.8	0.2	124	0.21
1162650	Rock	0.46	<0.005	<0.1	0.7	1.2	11	<0.1	1.8	0.5	220	0.43	<0.5	<0.5	<0.1	43	<0.1	<0.1	<0.1	6	19.13
1162651	Rock	1.60	0.050	1.6	16.0	2.2	62	0.1	51.2	16.8	806	3.60	2.4	43.7	7.1	126	<0.1	0.4	0.2	98	2.22
1162652	Rock	2.56	0.006	2.0	9.6	1.6	42	<0.1	30.9	9.9	643	2.77	2.1	5.5	7.8	63	<0.1	0.2	0.4	64	0.88
1162653	Rock	2.43	<0.005	2.1	9.7	2.7	33	<0.1	13.2	8.1	517	2.35	3.0	2.4	6.3	76	<0.1	0.8	0.3	49	1.01
1162654	Rock	3.70	0.132	2.1	34.1	5.5	43	0.6	9.3	6.9	520	2.19	10.9	138.2	5.1	134	0.1	5.4	0.1	48	2.49
1162655	Rock	1.91	0.125	3.4	14.7	7.5	47	0.5	7.3	6.8	777	2.51	4.2	121.1	3.7	216	0.1	2.8	<0.1	51	4.23
1162656	Rock	2.96	0.112	4.3	24.7	35.2	60	0.4	8.6	10.5	890	3.21	9.9	120.3	2.3	174	0.2	2.1	0.2	45	3.23
1162657	Rock	2.85	3.328	9.4	12.1	9.3	43	12.0	8.2	10.0	684	2.84	7.0	3791.6	2.0	158	0.3	1.5	0.8	19	1.77
1162658	Rock	3.01	0.502	3.1	8.7	4.8	31	2.0	9.7	8.5	764	2.65	2.8	494.6	4.6	145	0.3	0.7	0.2	25	2.30
1162659	Rock	3.93	0.098	1.8	11.5	5.1	41	0.2	9.0	6.9	533	2.40	3.1	91.0	4.5	121	0.1	0.5	<0.1	30	2.04
1162571	Rock	1.63	<0.005	2.1	17.5	4.4	38	<0.1	2.0	4.1	487	2.31	1.3	1.2	14.6	159	<0.1	0.7	<0.1	16	1.29
1162572	Rock	4.89	<0.005	1.5	15.1	4.9	42	<0.1	2.2	5.0	539	2.44	3.1	<0.5	16.9	454	<0.1	0.8	<0.1	18	1.32
1162573	Rock	1.50	<0.005	1.5	6.5	3.3	34	<0.1	1.8	4.2	495	2.12	2.4	1.8	14.7	85	<0.1	0.4	<0.1	15	0.76
1162574	Rock	1.44	<0.005	1.2	8.4	5.3	32	<0.1	1.7	3.6	586	1.97	1.4	2.2	13.8	414	0.1	0.6	<0.1	15	1.67
1162575	Rock	2.68	<0.005	0.9	8.9	4.4	30	<0.1	1.6	3.7	562	2.02	1.6	1.0	13.5	458	<0.1	0.6	<0.1	13	1.90
1162576	Rock	3.51	<0.005	1.1	8.7	4.4	37	<0.1	1.6	3.9	536	2.08	1.1	<0.5	12.0	91	<0.1	0.3	<0.1	16	1.27
1162577	Rock	3.76	<0.005	1.1	10.9	3.8	41	<0.1	1.6	4.5	514	2.34	1.5	<0.5	11.6	82	<0.1	0.3	<0.1	17	0.93
1162578	Rock	3.23	<0.005	1.2	9.0	6.9	43	<0.1	1.5	4.6	650	2.24	2.3	<0.5	9.4	926	0.1	0.4	<0.1	21	3.01
1162579	Rock	3.61	<0.005	1.4	10.4	7.2	38	<0.1	1.4	4.3	675	2.32	6.4	<0.5	11.2	1204	0.2	1.0	<0.1	26	2.76
1162580	Rock	0.88	<0.005	0.5	0.9	1.2	13	<0.1	1.6	0.6	214	0.45	<0.5	<0.5	0.1	50	<0.1	<0.1	<0.1	6	18.77
1162660	Rock	1.97	0.111	1.6	10.7	5.3	40	0.2	9.3	7.1	563	2.46	3.1	107.3	4.7	126	0.1	0.7	<0.1	31	2.18



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm
1162600	Rock Pulp	0.062	12	44	0.86	246	0.096	<20	1.48	0.079	0.19	8.7	0.74	4.4	1.4	1.46	6	3.9	0.6	
1162601	Rock	0.035	10	20	0.14	2704	0.001	<20	0.75	0.011	0.22	0.9	1.66	27.1	1.4	0.06	2	<0.5	<0.2	
1162602	Rock	0.035	6	21	0.18	2468	<0.001	<20	0.63	0.008	0.22	0.7	1.62	22.1	0.9	0.06	2	<0.5	<0.2	
1162603	Rock	0.046	5	15	0.15	2041	0.001	<20	0.63	0.009	0.19	0.7	1.84	23.3	1.2	<0.05	2	<0.5	<0.2	
1162604	Rock	0.063	4	12	0.18	403	0.001	<20	0.61	0.014	0.25	0.3	1.59	27.7	0.7	<0.05	2	<0.5	<0.2	
1162605	Rock	0.062	7	23	0.19	4028	0.003	<20	0.62	0.031	0.28	0.6	1.46	32.9	0.5	0.10	2	<0.5	<0.2	
1162606	Rock	0.062	6	20	0.25	1060	0.010	<20	0.70	0.057	0.35	0.5	0.71	25.5	0.8	<0.05	3	<0.5	<0.2	
1162607	Rock	0.063	7	38	0.49	1373	0.026	<20	0.99	0.035	0.59	0.2	0.53	26.6	0.4	<0.05	4	<0.5	<0.2	
1162608	Rock	0.059	7	26	0.83	691	0.067	<20	1.33	0.030	0.95	0.4	0.38	22.2	0.5	<0.05	5	<0.5	<0.2	
1162650	Rock	0.014	<1	<1	12.31	16	<0.001	<20	0.02	0.001	0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2	
1162651	Rock	0.058	17	144	1.66	731	0.117	<20	1.83	0.055	1.17	0.2	0.05	13.2	0.4	<0.05	7	<0.5	<0.2	
1162652	Rock	0.059	15	78	1.12	730	0.146	<20	1.51	0.039	1.10	0.4	0.05	9.1	0.4	<0.05	6	<0.5	<0.2	
1162653	Rock	0.042	9	24	0.49	404	0.049	<20	1.03	0.013	0.55	0.2	0.19	10.1	0.2	<0.05	4	<0.5	<0.2	
1162654	Rock	0.015	9	16	0.46	1090	0.005	<20	0.47	0.004	0.15	0.4	0.30	10.2	<0.1	0.09	1	<0.5	0.4	
1162655	Rock	0.006	5	21	1.05	923	0.004	<20	0.53	0.005	0.17	0.2	0.24	10.9	<0.1	0.06	1	<0.5	0.3	
1162656	Rock	0.003	4	13	0.49	1404	0.001	<20	0.53	0.004	0.24	0.2	0.30	12.4	0.1	<0.05	2	<0.5	0.3	
1162657	Rock	0.004	4	9	0.61	2750	<0.001	<20	0.36	0.018	0.18	0.5	0.48	8.4	<0.1	0.17	1	<0.5	7.0	
1162658	Rock	0.022	12	10	0.92	1463	0.002	<20	0.28	0.046	0.16	0.7	0.24	9.2	<0.1	0.26	<1	<0.5	1.2	
1162659	Rock	0.026	14	10	0.76	1061	0.002	<20	0.39	0.035	0.26	0.5	0.16	7.6	<0.1	0.11	1	<0.5	<0.2	
1162571	Rock	0.045	42	11	0.46	421	0.085	<20	0.85	0.055	0.53	0.7	0.08	2.2	0.2	0.22	5	<0.5	<0.2	
1162572	Rock	0.051	49	7	0.52	1058	0.103	<20	0.97	0.068	0.63	2.9	0.07	2.4	0.3	0.22	6	<0.5	<0.2	
1162573	Rock	0.043	44	6	0.54	383	0.125	<20	1.05	0.060	0.69	0.7	0.08	1.6	0.3	0.11	6	<0.5	<0.2	
1162574	Rock	0.043	41	5	0.45	439	0.063	<20	0.71	0.060	0.41	0.5	0.19	2.6	0.2	0.14	4	<0.5	<0.2	
1162575	Rock	0.039	42	6	0.43	378	0.072	<20	0.79	0.062	0.50	0.6	0.10	2.2	0.2	0.24	4	<0.5	<0.2	
1162576	Rock	0.043	40	5	0.49	279	0.098	<20	0.85	0.055	0.60	0.7	0.06	2.1	0.2	0.19	5	<0.5	<0.2	
1162577	Rock	0.050	40	5	0.55	346	0.112	<20	0.94	0.068	0.67	1.0	0.13	2.2	0.3	0.23	5	<0.5	<0.2	
1162578	Rock	0.062	34	4	0.51	720	0.094	<20	0.73	0.063	0.51	0.9	0.22	2.7	0.2	0.22	4	<0.5	<0.2	
1162579	Rock	0.063	34	5	0.44	1292	0.058	<20	0.46	0.067	0.25	0.7	0.59	3.3	0.1	0.26	3	<0.5	<0.2	
1162580	Rock	0.019	<1	1	11.90	17	0.002	<20	0.06	0.001	0.04	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2	
1162660	Rock	0.028	16	10	0.81	993	0.002	<20	0.39	0.038	0.25	0.5	0.14	8.0	<0.1	0.11	1	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 5 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162661	Rock	2.61	0.179	1.4	9.0	7.0	44	0.2	8.6	6.9	708	2.33	2.0	181.1	5.1	141	0.1	0.5	<0.1	30	2.43
1162662	Rock	3.27	0.100	1.7	13.6	6.2	50	0.1	8.0	7.4	642	2.64	2.8	84.9	3.7	144	0.1	0.8	<0.1	30	2.07
1162663	Rock	2.77	1.147	2.2	7.6	8.4	32	3.7	7.9	7.2	733	2.46	2.9	1061.3	3.0	141	0.2	0.9	0.2	19	2.22
1162664	Rock	2.51	0.294	2.4	17.1	5.7	42	0.8	7.3	7.7	676	2.41	2.7	400.6	4.9	120	0.2	1.1	0.1	22	1.94
1162665	Rock	2.23	0.850	2.5	9.9	9.0	51	1.5	6.6	8.5	727	2.48	2.3	512.3	5.5	137	0.3	1.1	0.1	26	2.39
1162666	Rock	3.30	0.341	2.5	7.0	13.1	56	1.0	6.2	6.2	723	2.25	1.9	307.3	6.4	145	0.3	0.7	<0.1	27	2.36
1162667	Rock	3.30	0.101	2.9	6.7	13.8	49	0.3	6.8	6.7	752	2.19	3.6	105.9	6.6	144	0.2	0.4	<0.1	25	2.22
1162668	Rock	1.95	0.036	2.8	4.2	10.5	44	0.1	7.7	6.4	739	2.15	5.0	30.0	9.3	132	0.2	0.5	<0.1	28	2.28
1162669	Rock	2.86	0.013	1.8	9.0	6.3	37	<0.1	6.3	5.7	468	1.85	2.0	21.7	8.0	103	<0.1	0.4	<0.1	23	1.80
1162679	Rock	1.49	0.038	1.5	21.9	43.8	61	0.2	14.0	6.5	549	2.15	2.0	15.0	6.4	32	0.1	0.5	0.2	38	0.45
1162680	Rock	0.53	<0.005	0.1	2.2	1.2	11	<0.1	3.9	0.6	228	0.46	<0.5	1.0	<0.1	51	<0.1	<0.1	<0.1	5	18.13
1162681	Rock	1.95	<0.005	0.8	36.5	12.1	57	<0.1	25.1	9.5	570	2.12	1.8	1.9	6.0	18	0.1	0.4	0.2	41	0.25
1162682	Rock	3.05	0.006	0.6	97.7	3.1	61	<0.1	22.6	15.4	706	3.15	1.9	3.2	2.2	31	0.1	0.4	<0.1	104	0.52
1162683	Rock	1.57	0.010	0.5	173.3	2.0	78	<0.1	12.7	21.3	813	4.41	2.7	7.0	0.6	34	0.1	1.0	<0.1	159	0.81
1162684	Rock	1.80	0.012	0.6	139.9	3.8	75	<0.1	23.6	20.4	969	4.66	3.3	11.1	0.7	71	<0.1	0.8	<0.1	181	0.81
1162685	Rock	1.94	0.005	0.4	132.1	1.4	54	<0.1	42.2	18.6	643	3.56	1.8	4.4	0.4	33	<0.1	0.4	<0.1	127	0.82
1162686	Rock	2.07	<0.005	0.4	92.3	3.6	37	<0.1	48.2	13.4	427	2.37	1.2	2.1	5.0	23	<0.1	0.4	<0.1	72	0.67
1162687	Rock	2.23	0.005	0.6	48.8	6.7	62	<0.1	15.8	10.2	528	2.62	1.9	3.1	7.3	32	<0.1	0.9	<0.1	61	0.34
1162688	Rock	2.10	0.008	0.6	97.8	3.1	70	<0.1	17.5	15.3	680	3.49	1.8	1.5	0.9	33	<0.1	1.1	<0.1	88	0.59
1162689	Rock	2.11	0.006	0.5	96.4	1.3	48	<0.1	34.9	16.0	697	3.06	2.9	2.0	1.2	24	<0.1	1.3	<0.1	91	0.60
1162690	Rock	1.78	0.007	0.5	96.8	3.3	53	<0.1	38.3	17.3	744	3.14	3.2	2.6	1.2	26	<0.1	1.4	<0.1	95	0.60
1162691	Rock	1.88	<0.005	0.5	94.7	1.6	51	<0.1	57.7	19.4	767	3.65	5.6	1.0	1.0	36	<0.1	1.5	<0.1	113	0.57
1162692	Rock	2.09	<0.005	0.5	56.0	2.3	77	<0.1	82.1	18.2	874	3.61	6.9	1.3	0.6	53	<0.1	1.2	<0.1	86	0.57
1162693	Rock	2.11	<0.005	0.7	14.9	2.2	81	<0.1	7.7	10.3	744	3.76	1.6	0.8	0.5	28	<0.1	0.6	<0.1	69	0.44
1162694	Rock	2.01	<0.005	0.6	54.8	1.5	80	<0.1	15.0	18.7	810	4.06	1.5	1.5	0.4	53	<0.1	0.5	<0.1	116	0.58
1162695	Rock	2.12	0.007	0.6	56.5	1.0	55	<0.1	20.5	21.1	577	3.96	0.6	0.7	0.3	36	<0.1	0.1	<0.1	124	0.63
1162696	Rock	2.34	<0.005	0.6	66.8	1.9	59	<0.1	18.3	17.8	693	3.13	0.9	0.8	2.1	44	<0.1	0.3	0.1	84	0.66
1162697	Rock	2.00	<0.005	0.8	45.2	1.3	40	<0.1	19.7	14.1	842	2.78	2.8	0.7	0.6	48	<0.1	0.5	<0.1	78	0.83
1162698	Rock	2.26	<0.005	0.6	25.7	1.2	50	<0.1	12.9	17.6	488	3.82	0.7	<0.5	0.4	31	<0.1	0.1	<0.1	101	0.78
1162699	Rock	1.99	<0.005	0.6	21.8	1.2	52	<0.1	12.6	18.3	478	3.87	0.7	<0.5	0.5	56	<0.1	0.2	<0.1	117	1.31



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1162661	Rock	0.034	16	10	0.93	1369	0.003	<20	0.31	0.037	0.21	0.7	0.09	8.4	<0.1	0.13	<1	<0.5	<0.2
1162662	Rock	0.025	11	10	0.78	1430	0.002	<20	0.42	0.035	0.27	0.7	0.08	8.1	<0.1	0.25	2	<0.5	<0.2
1162663	Rock	0.016	7	9	0.89	947	0.002	<20	0.29	0.033	0.18	0.7	0.38	8.8	<0.1	0.37	<1	<0.5	2.2
1162664	Rock	0.028	11	11	0.80	792	0.004	<20	0.39	0.037	0.25	1.0	0.16	8.6	<0.1	0.45	1	<0.5	0.5
1162665	Rock	0.041	9	11	0.98	591	0.006	<20	0.25	0.050	0.16	2.1	0.13	10.2	<0.1	0.66	<1	<0.5	1.1
1162666	Rock	0.038	9	10	0.89	855	0.003	<20	0.25	0.046	0.17	2.1	0.15	8.1	<0.1	0.52	1	<0.5	0.8
1162667	Rock	0.046	12	9	0.82	1389	0.004	<20	0.28	0.045	0.17	1.0	0.09	8.6	<0.1	0.29	1	<0.5	0.3
1162668	Rock	0.052	18	12	0.87	899	0.009	<20	0.31	0.056	0.18	0.9	0.11	8.6	<0.1	0.16	1	<0.5	<0.2
1162669	Rock	0.042	16	12	0.64	898	0.010	<20	0.47	0.038	0.31	0.7	0.13	6.4	<0.1	0.09	2	<0.5	<0.2
1162679	Rock	0.040	25	36	0.72	728	0.127	<20	1.19	0.038	0.73	0.6	0.06	4.9	0.3	<0.05	5	<0.5	<0.2
1162680	Rock	0.013	<1	6	11.57	32	<0.001	<20	0.02	0.002	0.01	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1162681	Rock	0.064	30	56	0.95	432	0.129	<20	1.47	0.030	0.97	0.9	0.05	5.5	0.3	<0.05	6	<0.5	<0.2
1162682	Rock	0.069	8	46	1.19	800	0.189	<20	1.65	0.074	0.89	0.5	0.03	9.1	0.2	<0.05	7	<0.5	<0.2
1162683	Rock	0.121	3	14	1.06	544	0.124	<20	1.68	0.072	0.58	0.3	0.03	12.9	<0.1	<0.05	8	<0.5	<0.2
1162684	Rock	0.110	5	46	1.33	1456	0.167	<20	1.90	0.091	0.73	0.3	0.04	14.4	0.1	<0.05	9	<0.5	<0.2
1162685	Rock	0.088	2	99	1.40	849	0.184	<20	1.72	0.101	0.65	0.2	0.04	9.8	0.1	<0.05	7	<0.5	<0.2
1162686	Rock	0.058	11	122	1.28	469	0.146	<20	1.41	0.099	0.52	0.3	0.02	7.0	0.1	<0.05	5	<0.5	<0.2
1162687	Rock	0.045	21	29	0.72	776	0.146	<20	1.26	0.044	0.80	0.4	0.03	4.5	0.2	<0.05	5	<0.5	<0.2
1162688	Rock	0.064	3	39	1.25	501	0.169	<20	1.87	0.086	0.87	0.3	0.03	8.3	0.1	<0.05	7	<0.5	<0.2
1162689	Rock	0.044	6	102	1.36	251	0.112	<20	1.44	0.117	0.44	0.5	0.03	10.9	<0.1	<0.05	6	<0.5	<0.2
1162690	Rock	0.044	6	107	1.43	274	0.112	<20	1.52	0.111	0.49	0.4	0.03	11.0	<0.1	<0.05	6	<0.5	<0.2
1162691	Rock	0.057	5	130	1.66	388	0.158	<20	1.71	0.077	0.76	0.5	0.02	10.8	0.2	<0.05	6	<0.5	<0.2
1162692	Rock	0.083	4	137	1.48	605	0.111	<20	1.61	0.057	0.50	0.5	0.04	9.2	0.1	<0.05	6	<0.5	<0.2
1162693	Rock	0.101	3	9	0.69	279	0.132	<20	1.11	0.067	0.46	0.3	0.03	9.2	<0.1	<0.05	6	<0.5	<0.2
1162694	Rock	0.074	2	22	1.12	462	0.172	<20	1.55	0.070	0.65	0.2	0.06	9.7	<0.1	<0.05	7	<0.5	<0.2
1162695	Rock	0.061	2	77	2.11	320	0.245	<20	2.30	0.090	1.25	0.2	0.02	8.8	0.2	<0.05	7	<0.5	<0.2
1162696	Rock	0.056	7	48	1.51	403	0.199	<20	1.76	0.067	0.89	0.2	0.03	5.9	0.2	<0.05	6	<0.5	<0.2
1162697	Rock	0.058	3	98	1.52	757	0.185	<20	1.50	0.104	0.56	0.3	0.03	7.9	0.1	<0.05	6	<0.5	<0.2
1162698	Rock	0.037	2	65	2.15	652	0.237	<20	2.35	0.118	1.22	0.1	0.02	8.7	0.2	<0.05	8	<0.5	<0.2
1162699	Rock	0.060	3	68	2.13	660	0.229	<20	2.26	0.105	1.23	<0.1	0.01	10.6	0.2	<0.05	8	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1162700	Rock Pulp	0.12	2.231	54.2	2150.0	1230.0	3548	26.4	173.8	19.3	592	4.83	1108.1	2544.2	2.4	76	22.0	15.8	10.0	52	1.42	
1162701	Rock	2.27	<0.005	0.8	17.3	1.3	56	<0.1	13.0	18.9	758	4.18	1.2	<0.5	0.8	102	<0.1	0.5	<0.1	113	3.17	
1162702	Rock	2.07	<0.005	0.8	8.8	1.7	66	<0.1	16.5	17.5	879	4.11	1.0	<0.5	0.9	167	<0.1	0.7	<0.1	84	3.65	
1162703	Rock	2.21	<0.005	1.1	14.9	2.7	64	<0.1	53.8	15.2	978	3.42	2.2	<0.5	0.6	168	<0.1	1.9	<0.1	66	3.56	
1162704	Rock	1.88	<0.005	1.3	15.1	2.5	83	<0.1	11.5	10.9	1142	3.85	4.7	1.6	0.8	111	<0.1	0.8	<0.1	66	2.66	
1162705	Rock	2.05	<0.005	1.1	16.2	1.4	74	<0.1	27.3	17.1	1754	3.81	0.7	1.8	1.3	130	<0.1	0.4	<0.1	94	3.57	
1162706	Rock	1.93	<0.005	0.6	15.6	1.7	48	<0.1	40.0	19.9	1749	3.11	0.7	1.1	1.7	152	<0.1	0.2	<0.1	100	3.72	
1162707	Rock	1.99	0.007	0.9	62.5	1.4	34	<0.1	97.3	17.1	592	2.10	0.8	3.8	0.6	112	<0.1	0.1	<0.1	60	2.68	
1162708	Rock	2.56	0.006	0.8	52.0	3.5	20	<0.1	88.3	13.4	438	1.50	0.6	0.6	0.8	153	<0.1	<0.1	<0.1	40	4.02	
1162709	Rock	2.39	0.007	1.2	46.2	1.9	44	<0.1	58.4	17.4	749	2.55	1.2	<0.5	0.6	92	<0.1	0.2	<0.1	66	2.47	
1162710	Rock Pulp	0.12	1.214	4.0	32.3	5.0	48	0.2	23.0	8.7	379	2.35	6.0	505.6	0.8	39	0.2	0.8	0.1	56	0.79	
1162711	Rock	2.71	0.007	1.0	110.9	1.3	67	<0.1	18.9	18.3	693	3.37	0.7	1.9	0.3	46	<0.1	<0.1	<0.1	78	1.30	
1162712	Rock	2.19	<0.005	1.0	69.8	2.9	74	<0.1	45.7	20.2	811	3.60	1.8	0.8	0.6	170	<0.1	0.2	<0.1	121	2.63	
1162713	Rock	1.79	<0.005	1.2	48.5	2.4	74	<0.1	21.3	20.1	721	3.71	1.5	<0.5	0.5	83	<0.1	0.2	<0.1	103	2.17	
1162714	Rock	2.19	<0.005	1.5	85.3	2.4	67	<0.1	24.0	22.3	988	4.17	0.8	1.2	0.4	130	<0.1	0.3	<0.1	148	2.95	
1162715	Rock	1.73	0.010	1.0	52.1	4.6	72	<0.1	30.4	22.2	817	4.06	1.2	4.0	1.1	206	0.2	0.4	<0.1	139	3.57	
1162716	Rock	1.84	<0.005	0.8	17.0	5.1	73	<0.1	26.3	17.8	787	3.19	1.7	0.5	1.4	455	0.1	0.3	<0.1	106	4.33	
1162717	Rock	1.99	<0.005	1.3	50.4	3.1	66	<0.1	57.0	22.0	860	4.01	1.5	1.5	1.0	151	0.1	0.4	<0.1	125	3.45	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000284.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1162700	Rock Pulp	0.063	11	43	0.82	190	0.085	<20	1.39	0.075	0.18	7.8	0.69	4.1	1.3	1.48	6	3.7	0.6
1162701	Rock	0.057	5	61	1.89	959	0.182	<20	2.14	0.067	1.48	<0.1	0.02	16.6	0.3	<0.05	7	<0.5	<0.2
1162702	Rock	0.060	6	39	1.75	398	0.105	<20	1.71	0.032	1.11	<0.1	0.03	16.4	0.2	<0.05	5	<0.5	<0.2
1162703	Rock	0.069	3	95	1.02	485	0.079	<20	1.01	0.050	0.52	0.2	0.09	12.4	0.1	<0.05	4	<0.5	<0.2
1162704	Rock	0.076	6	8	0.83	290	0.062	<20	0.99	0.062	0.55	0.2	0.17	16.9	0.1	<0.05	4	<0.5	<0.2
1162705	Rock	0.068	8	104	1.35	259	0.094	<20	1.31	0.053	0.70	0.2	0.03	16.7	0.2	<0.05	6	<0.5	<0.2
1162706	Rock	0.058	9	203	2.44	736	0.078	<20	1.70	0.063	0.23	0.1	0.02	12.9	<0.1	<0.05	7	<0.5	<0.2
1162707	Rock	0.035	3	290	1.85	399	0.094	<20	1.38	0.081	0.27	0.1	0.02	6.2	<0.1	<0.05	4	<0.5	<0.2
1162708	Rock	0.033	2	277	1.45	216	0.112	<20	1.08	0.082	0.35	<0.1	0.01	4.0	<0.1	<0.05	3	<0.5	<0.2
1162709	Rock	0.060	2	141	1.77	459	0.145	<20	1.74	0.043	0.80	0.2	0.05	5.5	0.2	<0.05	5	<0.5	<0.2
1162710	Rock Pulp	0.053	4	29	0.69	88	0.125	<20	1.42	0.080	0.13	9.9	0.04	4.6	<0.1	<0.05	5	<0.5	<0.2
1162711	Rock	0.056	1	35	1.54	321	0.233	<20	2.15	0.050	1.32	0.2	0.02	4.6	0.2	<0.05	6	<0.5	<0.2
1162712	Rock	0.056	2	122	1.55	294	0.193	<20	1.77	0.063	0.88	0.3	0.02	7.6	0.2	<0.05	6	<0.5	<0.2
1162713	Rock	0.064	2	37	1.64	304	0.218	<20	2.01	0.043	1.27	0.2	0.05	8.0	0.2	<0.05	7	<0.5	<0.2
1162714	Rock	0.053	2	54	1.88	374	0.206	<20	2.14	0.042	1.47	0.2	0.01	11.7	0.3	<0.05	7	<0.5	<0.2
1162715	Rock	0.058	6	99	1.75	178	0.112	<20	1.63	0.050	0.71	0.2	0.03	17.1	0.2	<0.05	7	<0.5	<0.2
1162716	Rock	0.056	6	106	1.57	731	0.180	<20	1.11	0.047	0.74	0.3	<0.01	9.4	0.2	<0.05	6	<0.5	<0.2
1162717	Rock	0.050	5	179	2.17	235	0.137	<20	2.05	0.046	1.18	0.1	0.06	16.8	0.3	<0.05	7	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000284.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1162609	Rock	1.68	0.024	2.9	41.3	12.9	49	<0.1	10.7	14.5	927	3.27	39.1	20.0	6.7	74	0.1	2.2	0.2	67	0.14
REP 1162609	QC	0.025																			
1162626	Rock	3.08	<0.005	1.4	18.1	6.0	76	<0.1	8.5	21.3	747	4.70	24.3	1.3	1.7	278	<0.1	1.3	<0.1	73	8.23
REP 1162626	QC	1.5 17.9 6.2 78 <0.1 8.6 21.9 762 4.76 24.4 0.6 1.7 280 0.1 1.2 <0.1 74 8.41																			
1162631	Rock	3.52	<0.005	1.0	22.3	4.1	61	<0.1	6.7	16.1	807	4.05	10.9	<0.5	1.5	169	<0.1	2.0	<0.1	92	3.17
REP 1162631	QC	1.1 22.4 4.1 61 <0.1 7.1 16.2 805 4.00 10.6 0.8 1.6 167 <0.1 2.0 <0.1 89 3.14																			
1162636	Rock	2.66	0.093	0.7	13.5	2.3	76	0.2	30.0	20.6	847	4.86	4.5	430.6	1.6	211	<0.1	1.0	<0.1	127	3.89
REP 1162636	QC	0.125																			
1162654	Rock	3.70	0.132	2.1	34.1	5.5	43	0.6	9.3	6.9	520	2.19	10.9	138.2	5.1	134	0.1	5.4	0.1	48	2.49
REP 1162654	QC	0.132																			
1162656	Rock	2.96	0.112	4.3	24.7	35.2	60	0.4	8.6	10.5	890	3.21	9.9	120.3	2.3	174	0.2	2.1	0.2	45	3.23
REP 1162656	QC	4.4 24.7 36.1 63 0.4 8.8 10.5 898 3.24 10.1 110.4 2.4 176 0.2 2.1 0.2 45 3.26																			
1162690	Rock	1.78	0.007	0.5	96.8	3.3	53	<0.1	38.3	17.3	744	3.14	3.2	2.6	1.2	26	<0.1	1.4	<0.1	95	0.60
REP 1162690	QC	0.5 97.9 3.3 54 <0.1 39.6 17.6 762 3.22 3.2 2.1 1.1 25 <0.1 1.4 <0.1 96 0.61																			
1162698	Rock	2.26	<0.005	0.6	25.7	1.2	50	<0.1	12.9	17.6	488	3.82	0.7	<0.5	0.4	31	<0.1	0.1	<0.1	101	0.78
REP 1162698	QC	<0.005																			
Core Reject Duplicates																					
1162629	Rock	3.23	<0.005	1.0	5.3	4.6	70	<0.1	8.4	15.4	746	3.51	19.7	1.8	1.2	144	<0.1	2.0	<0.1	74	3.03
DUP 1162629	QC	0.026 0.9 5.0 4.3 70 <0.1 9.2 15.7 740 3.49 19.3 <0.5 1.2 142 <0.1 2.1 <0.1 72 2.98																			
1162635	Rock	3.62	<0.005	1.1	17.7	4.5	65	<0.1	9.6	19.4	814	4.52	36.7	0.7	1.6	219	0.1	2.7	<0.1	116	4.31
DUP 1162635	QC	<0.005 1.2 17.5 4.7 69 <0.1 9.6 19.8 796 4.52 39.6 0.6 1.6 224 0.1 3.0 <0.1 122 4.28																			
1162659	Rock	3.93	0.098	1.8	11.5	5.1	41	0.2	9.0	6.9	533	2.40	3.1	91.0	4.5	121	0.1	0.5	<0.1	30	2.04
DUP 1162659	QC	0.101 1.7 11.0 5.1 40 0.2 8.7 6.9 533 2.43 3.3 88.5 4.6 123 0.2 0.6 <0.1 29 2.06																			
1162692	Rock	2.09	<0.005	0.5	56.0	2.3	77	<0.1	82.1	18.2	874	3.61	6.9	1.3	0.6	53	<0.1	1.2	<0.1	86	0.57
DUP 1162692	QC	0.006 0.5 60.2 2.4 85 <0.1 86.8 19.4 905 3.90 7.3 1.5 0.7 57 <0.1 1.2 <0.1 91 0.59																			
Reference Materials																					
STD DS10	Standard	12.7 158.1 150.5 357 1.8 71.7 13.1 845 2.71 43.2 72.4 7.4 66 2.9 9.2 12.4 42 1.05																			
STD DS10	Standard	14.1 159.6 146.5 364 1.9 74.3 12.9 871 2.71 48.6 57.9 7.3 70 3.0 9.0 12.6 42 1.08																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Project: QVV
Report Date: October 06, 2016

Page: 1 of 3 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000284.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1162609	Rock	0.038	11	17	0.26	1058	0.007	<20	0.72	0.022	0.42	0.5	0.34	14.5	0.3	<0.05	2	<0.5	<0.2
REP 1162609	QC																		
1162626	Rock	0.058	9	10	0.72	194	0.013	<20	1.10	0.008	0.43	0.2	0.78	12.7	0.1	<0.05	3	<0.5	<0.2
REP 1162626	QC	0.057	9	9	0.74	198	0.014	<20	1.14	0.008	0.44	0.2	0.79	13.4	0.1	<0.05	4	<0.5	<0.2
1162631	Rock	0.088	9	11	0.45	716	0.032	<20	0.78	0.055	0.31	0.4	0.28	14.0	0.1	<0.05	4	<0.5	<0.2
REP 1162631	QC	0.089	9	11	0.45	733	0.032	<20	0.77	0.055	0.30	0.4	0.27	14.1	0.1	<0.05	4	<0.5	<0.2
1162636	Rock	0.068	11	89	1.70	510	0.082	<20	2.40	0.030	0.84	0.2	0.27	18.4	0.2	<0.05	9	<0.5	<0.2
REP 1162636	QC																		
1162654	Rock	0.015	9	16	0.46	1090	0.005	<20	0.47	0.004	0.15	0.4	0.30	10.2	<0.1	0.09	1	<0.5	0.4
REP 1162654	QC																		
1162656	Rock	0.003	4	13	0.49	1404	0.001	<20	0.53	0.004	0.24	0.2	0.30	12.4	0.1	<0.05	2	<0.5	0.3
REP 1162656	QC	0.003	4	13	0.50	1420	0.001	<20	0.54	0.004	0.24	0.2	0.31	12.7	<0.1	<0.05	1	<0.5	0.3
1162690	Rock	0.044	6	107	1.43	274	0.112	<20	1.52	0.111	0.49	0.4	0.03	11.0	<0.1	<0.05	6	<0.5	<0.2
REP 1162690	QC	0.046	6	110	1.45	275	0.114	<20	1.55	0.115	0.50	0.5	0.03	11.4	<0.1	<0.05	6	<0.5	<0.2
1162698	Rock	0.037	2	65	2.15	652	0.237	<20	2.35	0.118	1.22	0.1	0.02	8.7	0.2	<0.05	8	<0.5	<0.2
REP 1162698	QC																		
Core Reject Duplicates																			
1162629	Rock	0.097	7	26	0.78	219	0.071	<20	1.12	0.052	0.39	0.4	0.93	11.3	0.2	<0.05	4	<0.5	<0.2
DUP 1162629	QC	0.101	7	27	0.78	254	0.073	<20	1.11	0.051	0.38	0.4	0.90	11.7	0.2	<0.05	4	<0.5	<0.2
1162635	Rock	0.082	10	13	0.78	999	0.016	<20	1.38	0.037	0.24	0.2	1.73	17.8	<0.1	<0.05	5	<0.5	<0.2
DUP 1162635	QC	0.080	10	12	0.79	973	0.016	<20	1.38	0.037	0.24	0.2	1.81	18.6	<0.1	<0.05	6	<0.5	<0.2
1162659	Rock	0.026	14	10	0.76	1061	0.002	<20	0.39	0.035	0.26	0.5	0.16	7.6	<0.1	0.11	1	<0.5	<0.2
DUP 1162659	QC	0.026	14	10	0.76	1046	0.002	<20	0.39	0.035	0.26	0.5	0.16	7.8	<0.1	0.11	1	<0.5	<0.2
1162692	Rock	0.083	4	137	1.48	605	0.111	<20	1.61	0.057	0.50	0.5	0.04	9.2	0.1	<0.05	6	<0.5	<0.2
DUP 1162692	QC	0.086	4	148	1.55	640	0.121	<20	1.65	0.061	0.52	0.5	0.03	10.1	0.1	<0.05	6	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.072	17	54	0.76	397	0.082	<20	1.02	0.067	0.32	2.6	0.27	2.8	5.1	0.29	4	1.9	4.7
STD DS10	Standard	0.076	18	55	0.80	423	0.085	<20	1.04	0.071	0.35	3.2	0.28	3.0	5.3	0.27	4	2.0	5.2



QUALITY CONTROL REPORT

WHI16000284.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			14.0	155.6	132.9	347	2.0	73.1	12.4	843	2.63	43.9	72.2	6.6	64	2.8	8.7	11.8	41	1.04
STD DS10	Standard			14.3	159.9	154.4	365	2.3	72.9	12.9	906	2.79	46.0	80.2	8.3	68	3.0	8.5	12.7	44	1.10
STD OREAS45EA	Standard			1.6	685.5	14.5	30	0.3	383.3	52.6	406	21.24	11.6	50.8	10.0	4	<0.1	0.3	0.2	293	0.03
STD OREAS45EA	Standard			1.7	722.4	15.3	30	0.3	407.3	54.0	413	22.67	11.7	51.8	10.4	4	<0.1	0.4	0.3	315	0.04
STD OREAS45EA	Standard			1.7	690.3	13.8	30	0.3	390.8	54.0	413	23.03	11.1	44.9	9.6	4	<0.1	0.3	0.3	303	0.03
STD OREAS45EA	Standard			1.7	720.3	14.6	32	0.3	399.8	55.5	427	22.78	11.4	62.7	10.3	4	<0.1	0.3	0.3	309	0.03
STD OXD108	Standard		0.426																		
STD OXD108	Standard		0.422																		
STD OXD108	Standard		0.405																		
STD OXI121	Standard		1.811																		
STD OXI121	Standard		1.782																		
STD OXI121	Standard		1.809																		
STD OXN117	Standard		7.580																		
STD OXN117	Standard		7.649																		
STD OXN117	Standard		7.640																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		



QUALITY CONTROL REPORT

WHI16000284.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.071	17	52	0.74	387	0.079	<20	0.99	0.066	0.32	3.1	0.25	2.9	4.6	0.29	4	2.1	4.7
STD DS10	Standard	0.076	19	54	0.79	413	0.087	<20	1.06	0.076	0.35	3.0	0.27	3.1	5.5	0.28	4	2.1	4.8
STD OREAS45EA	Standard	0.027	7	776	0.09	151	0.101	<20	3.31	0.019	0.06	<0.1	0.01	76.5	<0.1	<0.05	13	1.1	<0.2
STD OREAS45EA	Standard	0.029	8	835	0.10	151	0.110	<20	3.41	0.016	0.06	<0.1	0.03	83.5	<0.1	<0.05	13	1.2	<0.2
STD OREAS45EA	Standard	0.028	7	840	0.10	145	0.106	<20	3.23	0.019	0.06	<0.1	0.01	78.8	<0.1	<0.05	13	0.9	<0.2
STD OREAS45EA	Standard	0.028	8	830	0.10	152	0.105	<20	3.38	0.026	0.06	<0.1	0.01	81.8	<0.1	<0.05	14	1.2	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	4	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000284.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
BLK	Blank	<0.005																				
Prep Wash																						
ROCK-WHI	Prep Blank	<0.005	0.8	3.8	2.0	34	<0.1	1.2	3.8	435	1.79	1.1	<0.5	2.7	32	<0.1	<0.1	<0.1	22	0.64		
ROCK-WHI	Prep Blank	<0.005	0.8	4.1	1.5	31	<0.1	1.0	3.5	410	1.66	0.8	<0.5	2.6	27	<0.1	<0.1	<0.1	23	0.61		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI1600284.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2		
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.041	6	4	0.40	75	0.100	<20	0.95	0.096	0.10	0.2	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.040	5	3	0.37	69	0.096	<20	0.89	0.089	0.09	0.2	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 19, 2016
Report Date: October 06, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000285.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-09-Rock-RAB
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162718	Rock	2.05	<0.005	1.2	17.8	2.4	68	<0.1	21.7	20.8	794	3.94	2.4	<0.5	0.9	201	<0.1	0.4	<0.1	98	3.82
1162719	Rock	2.21	<0.005	4.1	76.5	4.9	87	0.1	41.5	26.9	1219	5.21	5.8	1.3	1.6	249	0.2	0.8	<0.1	137	4.31
1162720	Rock	0.71	<0.005	0.2	1.7	1.5	16	<0.1	2.0	0.6	213	0.44	<0.5	<0.5	0.1	57	<0.1	<0.1	<0.1	<2	20.57
1162721	Rock	2.01	0.022	2.7	27.1	8.5	85	<0.1	18.9	17.5	1208	4.04	1.7	16.7	1.1	218	0.2	0.4	<0.1	81	4.54
1162722	Rock	2.02	0.027	11.4	37.4	7.0	83	0.1	7.2	14.4	1142	4.03	2.9	23.4	0.5	187	0.4	1.5	<0.1	63	3.97
1162723	Rock	2.14	0.187	105.8	40.5	25.6	80	0.5	15.3	15.7	978	3.70	11.0	164.8	0.3	221	0.6	1.7	0.5	57	4.66
1162724	Rock	1.90	0.015	9.4	37.3	5.8	100	<0.1	26.3	21.8	1011	4.67	2.5	12.5	0.8	136	0.2	1.4	<0.1	113	4.22
1162725	Rock	2.02	0.010	5.7	99.6	4.0	104	0.2	19.5	24.4	1192	5.38	1.2	6.6	1.5	132	0.2	4.2	<0.1	170	3.95
1162726	Rock	2.04	<0.005	1.8	84.5	4.8	86	0.1	13.1	21.8	1081	4.92	1.0	<0.5	3.0	147	0.2	2.0	<0.1	148	3.63
1162727	Rock	2.15	<0.005	1.6	9.7	3.4	50	<0.1	9.9	19.4	1004	4.53	13.5	<0.5	1.9	174	<0.1	1.9	0.3	84	3.70
1162728	Rock	2.10	<0.005	1.3	13.3	3.8	49	<0.1	8.6	19.9	925	4.52	46.0	<0.5	1.5	173	<0.1	1.5	0.4	84	3.69
1162729	Rock	2.05	<0.005	1.8	47.2	5.7	54	<0.1	26.1	21.5	1009	5.23	37.6	<0.5	2.0	160	<0.1	1.3	0.2	97	3.56
1162730	Rock	1.57	<0.005	1.7	42.7	6.1	56	<0.1	25.4	20.4	974	4.95	35.6	<0.5	1.8	149	<0.1	1.3	0.2	90	3.52
1162731	Rock	1.77	<0.005	2.9	96.4	5.5	55	<0.1	30.7	22.1	845	4.90	2.8	<0.5	1.8	179	<0.1	1.2	<0.1	109	3.50
1162732	Rock	2.00	0.008	2.0	121.6	2.4	80	0.1	30.8	23.7	914	5.06	1.0	3.7	1.5	148	0.1	0.3	<0.1	158	3.02
1162733	Rock	1.98	<0.005	1.7	50.5	2.8	60	<0.1	30.9	24.0	894	5.12	0.8	<0.5	2.1	98	<0.1	0.2	<0.1	165	3.24
1162734	Rock	2.09	0.008	2.3	16.5	3.6	62	<0.1	33.3	18.6	924	4.12	0.6	<0.5	4.9	126	<0.1	0.3	0.4	90	2.88
1162735	Rock	2.20	0.141	13.7	12.1	11.3	62	0.6	7.3	7.5	1035	2.44	0.7	134.8	8.0	204	0.3	0.4	0.2	47	3.70
1162736	Rock	2.21	0.180	3.3	11.0	11.0	58	0.9	7.8	7.3	619	2.05	0.6	171.4	10.1	276	<0.1	0.2	0.1	35	2.39
1162737	Rock	1.96	0.037	3.2	4.7	6.4	47	0.2	7.8	7.6	576	2.03	1.0	34.4	11.0	82	<0.1	0.2	<0.1	26	1.71
1162738	Rock	2.01	0.094	2.5	8.1	12.1	55	0.5	7.5	7.8	681	2.13	0.9	96.3	10.5	240	<0.1	0.3	0.2	30	2.24
1162739	Rock	1.93	0.402	2.8	12.3	12.2	62	2.3	7.7	7.5	751	2.49	0.6	417.7	10.0	159	0.2	0.4	0.1	44	2.27
1162740	Rock Pulp	0.12	2.014	62.1	2192.1	1387.2	3579	26.7	183.3	19.3	650	5.37	1185.3	705.5	2.9	80	22.2	15.7	10.0	57	1.54
1162741	Rock	2.07	0.080	7.2	22.8	11.6	85	0.5	7.1	10.9	962	3.08	1.2	73.8	7.9	185	0.2	0.4	0.2	66	2.73
1162742	Rock	1.97	0.008	2.2	2.9	7.1	44	<0.1	6.9	7.4	772	2.18	1.9	3.2	7.2	134	<0.1	0.2	0.2	24	2.56
1162743	Rock	2.16	<0.005	2.0	2.5	6.3	47	<0.1	7.9	7.7	602	2.30	6.5	3.0	7.6	131	<0.1	0.2	<0.1	29	2.31
1162744	Rock	2.25	<0.005	1.7	3.1	4.9	39	<0.1	8.7	6.4	614	2.23	1.9	0.6	8.5	132	<0.1	0.2	<0.1	35	2.17
1162745	Rock	1.88	<0.005	2.2	4.8	5.7	29	<0.1	6.9	4.5	477	1.85	1.7	0.8	8.5	124	<0.1	0.2	<0.1	28	2.07
1162746	Rock	2.35	0.130	2.3	17.9	10.0	27	0.6	5.5	5.0	495	1.65	6.5	140.6	6.1	137	<0.1	0.5	0.2	17	1.87
1162747	Rock	2.14	0.006	3.0	12.6	4.0	36	<0.1	6.0	5.3	704	2.15	1.7	1.3	9.4	821	<0.1	0.2	0.2	22	1.67



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1162718	Rock	0.054	6	178	2.18	946	0.068	<20	1.93	0.047	0.53	<0.1	<0.01	16.2	<0.1	<0.05	7	<0.5	<0.2	
1162719	Rock	0.046	8	120	1.82	606	0.074	<20	1.61	0.042	1.10	0.2	0.05	24.4	0.3	<0.05	7	<0.5	<0.2	
1162720	Rock	0.016	<1	<1	12.79	51	0.001	<20	0.03	0.002	0.02	<0.1	<0.01	0.8	<0.1	<0.05	<1	<0.5	<0.2	
1162721	Rock	0.063	6	41	1.72	1862	0.022	<20	0.92	0.036	0.61	0.1	0.14	17.5	0.2	0.07	4	<0.5	<0.2	
1162722	Rock	0.055	3	16	1.64	549	0.013	<20	0.78	0.024	0.46	0.2	0.15	18.4	0.1	<0.05	2	<0.5	<0.2	
1162723	Rock	0.005	1	19	1.33	683	0.001	<20	0.48	0.006	0.20	<0.1	0.85	16.5	0.1	<0.05	1	<0.5	0.9	
1162724	Rock	0.003	2	64	2.14	228	0.023	<20	1.41	0.016	0.73	<0.1	0.99	21.3	0.2	<0.05	5	<0.5	<0.2	
1162725	Rock	0.008	4	44	2.28	661	0.064	<20	1.39	0.046	1.03	0.1	0.95	24.6	0.3	0.24	6	<0.5	<0.2	
1162726	Rock	0.039	7	50	2.19	665	0.082	<20	1.52	0.070	1.05	<0.1	0.32	21.4	0.3	0.13	7	<0.5	<0.2	
1162727	Rock	0.057	10	59	2.10	944	0.047	<20	1.49	0.036	0.79	<0.1	0.22	17.5	0.2	0.06	5	<0.5	<0.2	
1162728	Rock	0.050	7	24	1.71	999	0.028	<20	1.14	0.020	0.59	0.1	0.63	16.0	0.2	0.07	4	<0.5	<0.2	
1162729	Rock	0.113	8	16	1.40	299	0.017	<20	1.05	0.028	0.54	0.1	0.43	18.8	0.1	0.07	3	<0.5	<0.2	
1162730	Rock	0.110	8	15	1.39	305	0.018	<20	0.97	0.026	0.51	0.1	0.46	16.6	0.1	0.06	3	<0.5	<0.2	
1162731	Rock	0.111	8	20	1.58	298	0.042	<20	1.57	0.046	0.62	0.1	0.06	17.3	0.2	0.14	5	<0.5	<0.2	
1162732	Rock	0.118	7	30	2.21	554	0.163	<20	2.40	0.060	1.18	0.3	0.03	16.9	0.3	0.14	9	<0.5	<0.2	
1162733	Rock	0.123	10	38	2.23	205	0.088	<20	2.36	0.070	0.52	0.2	0.02	17.8	0.1	0.09	10	<0.5	<0.2	
1162734	Rock	0.080	12	126	2.08	613	0.104	<20	2.12	0.037	0.84	0.4	0.02	11.2	0.2	0.21	8	<0.5	<0.2	
1162735	Rock	0.051	16	18	1.03	1657	0.027	<20	0.60	0.056	0.38	0.3	0.13	9.1	0.1	0.09	3	<0.5	0.4	
1162736	Rock	0.051	18	21	0.72	1434	0.034	<20	0.56	0.053	0.35	0.6	0.16	7.6	0.1	0.11	3	<0.5	0.5	
1162737	Rock	0.048	15	23	0.72	574	0.043	<20	0.84	0.063	0.56	0.7	0.07	7.6	0.2	0.09	4	<0.5	<0.2	
1162738	Rock	0.047	17	21	0.78	1730	0.029	<20	0.60	0.058	0.38	0.9	0.13	7.0	0.2	0.24	3	<0.5	0.3	
1162739	Rock	0.046	16	22	0.79	973	0.035	<20	0.71	0.065	0.48	0.8	0.26	7.5	0.1	0.35	3	<0.5	1.4	
1162740	Rock Pulp	0.061	12	46	0.85	207	0.094	<20	1.50	0.084	0.19	8.2	0.74	4.3	1.3	1.50	6	3.6	0.6	
1162741	Rock	0.052	13	21	1.15	1326	0.034	<20	0.79	0.041	0.55	0.8	0.12	11.8	0.2	0.29	4	<0.5	0.3	
1162742	Rock	0.038	11	14	0.96	701	0.006	<20	0.67	0.009	0.38	0.2	0.06	5.7	0.1	0.07	2	<0.5	<0.2	
1162743	Rock	0.039	10	27	0.87	866	0.013	<20	0.85	0.009	0.45	0.2	0.09	6.4	0.1	0.08	3	<0.5	<0.2	
1162744	Rock	0.044	11	31	1.07	1046	0.055	<20	0.95	0.032	0.69	0.4	0.05	7.0	0.2	0.10	4	<0.5	<0.2	
1162745	Rock	0.041	13	21	0.73	875	0.034	<20	0.76	0.052	0.49	0.7	0.04	6.2	0.1	0.11	3	<0.5	<0.2	
1162746	Rock	0.028	7	12	0.60	1387	0.002	<20	0.47	0.013	0.27	0.5	0.12	5.2	<0.1	0.21	2	<0.5	0.4	
1162747	Rock	0.041	20	19	0.55	1647	0.038	<20	0.74	0.046	0.44	0.9	0.08	5.4	0.1	0.18	3	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162748	Rock	2.13	<0.005	2.5	4.7	1.8	32	<0.1	6.1	4.7	590	1.86	0.7	<0.5	8.0	557	<0.1	0.1	0.1	23	1.06
1162749	Rock	1.85	0.010	3.1	4.9	3.2	38	<0.1	5.7	4.7	672	2.08	0.6	5.3	7.0	384	<0.1	0.1	0.1	32	1.46
1162750	Rock	0.80	<0.005	0.1	1.3	1.8	17	<0.1	3.1	0.8	237	0.46	0.9	<0.5	0.2	57	<0.1	<0.1	<0.1	<2	20.35
1162751	Rock	2.16	0.015	2.7	8.2	3.9	47	<0.1	6.2	6.0	616	2.11	0.6	14.2	10.1	457	<0.1	0.1	0.1	32	1.57
1162752	Rock	2.27	0.023	2.8	11.0	4.4	37	0.1	5.6	5.1	628	2.00	0.7	27.5	8.1	279	<0.1	0.1	0.1	28	1.76
1162753	Rock	1.90	0.005	1.0	110.3	7.8	77	<0.1	27.2	26.5	1078	4.61	16.3	1.0	0.9	56	0.1	1.1	<0.1	131	1.09
1162754	Rock	1.94	<0.005	1.4	42.5	3.1	25	<0.1	8.4	9.9	394	2.05	5.0	<0.5	0.7	19	<0.1	0.3	<0.1	55	0.44
1162755	Rock	1.86	0.005	1.0	42.2	3.1	72	<0.1	32.5	27.0	932	4.58	17.3	1.5	1.1	38	0.2	0.4	<0.1	131	0.54
1162756	Rock	2.80	0.005	1.5	34.6	5.5	66	<0.1	17.7	27.5	973	4.79	22.8	3.1	1.5	64	0.2	1.4	0.1	121	0.36
1162757	Rock	3.43	<0.005	1.3	28.8	3.2	74	<0.1	19.0	23.0	841	4.64	17.1	<0.5	1.7	50	0.2	0.9	<0.1	116	0.41
1162758	Rock	1.59	<0.005	2.2	34.3	5.2	81	<0.1	22.4	27.1	1072	5.07	30.7	<0.5	1.6	50	0.2	1.1	<0.1	135	0.27
1162759	Rock	1.96	<0.005	2.3	24.1	3.4	83	<0.1	13.6	23.7	1098	4.87	31.9	<0.5	2.0	76	0.2	1.2	<0.1	123	0.23
1162760	Rock	1.62	0.005	2.2	23.3	3.3	78	<0.1	13.3	22.8	1076	4.79	31.7	<0.5	1.9	70	0.2	1.1	<0.1	116	0.23
1162761	Rock	2.20	0.015	3.0	61.8	3.5	82	<0.1	29.3	24.2	1143	5.04	33.3	11.5	1.5	80	0.2	1.6	<0.1	147	0.19
1162762	Rock	1.33	0.015	5.2	28.9	3.8	88	<0.1	27.7	28.5	1183	5.67	61.9	10.9	0.8	59	0.3	1.0	<0.1	178	0.12
1162763	Rock	1.81	0.078	5.0	84.4	3.3	109	0.3	8.7	18.5	1215	4.79	31.5	71.4	0.6	70	0.4	2.6	<0.1	124	0.13
1162764	Rock	2.07	0.041	2.7	79.9	2.9	111	0.2	3.0	14.0	953	4.20	12.2	35.3	0.8	59	0.4	1.3	<0.1	98	0.21
1162765	Rock	2.50	0.037	3.0	51.9	2.5	72	0.1	3.0	11.7	922	4.37	13.0	29.3	0.6	62	0.4	2.6	<0.1	111	0.19
1162766	Rock	2.01	0.094	9.7	27.8	12.2	69	0.2	14.1	14.7	1091	4.38	12.2	87.3	0.5	84	0.5	0.9	0.2	76	3.52
1162767	Rock	2.17	0.038	12.2	38.7	6.0	78	0.1	23.8	22.8	1039	4.22	5.8	31.6	0.3	163	0.2	1.1	<0.1	60	4.42
1162768	Rock	2.27	0.031	10.3	81.4	3.9	93	0.1	17.4	22.1	932	4.41	3.7	26.8	1.0	120	0.2	1.0	<0.1	101	2.98
1162769	Rock	2.70	0.007	39.2	58.5	33.9	91	0.2	16.5	21.6	1064	4.37	2.9	1.3	1.5	153	0.2	1.2	0.3	109	3.42
1162770	Rock Pulp	0.12	0.799	4.4	36.3	6.0	53	0.4	25.3	10.4	397	2.51	7.4	548.0	1.0	39	0.2	0.8	0.1	59	0.85
1162771	Rock	2.87	<0.005	1.7	32.7	1.8	71	<0.1	17.0	23.4	1015	4.66	1.8	<0.5	0.9	110	<0.1	0.1	<0.1	128	2.80
1162772	Rock	2.67	<0.005	4.3	18.0	2.3	69	<0.1	17.3	22.5	1096	4.36	1.7	0.7	4.3	139	<0.1	0.2	0.1	120	3.11
1162773	Rock	2.18	0.006	1.1	16.1	2.6	81	<0.1	20.4	24.6	1192	5.01	1.9	3.3	1.1	181	<0.1	0.3	<0.1	131	3.88
1162774	Rock	2.63	0.176	3.3	24.2	4.8	91	0.4	14.5	23.9	1022	4.80	3.1	193.1	1.1	166	0.1	0.5	<0.1	123	3.89
1162775	Rock	2.72	0.025	2.0	17.5	4.4	58	<0.1	16.2	14.1	871	3.12	8.9	18.8	3.3	155	<0.1	0.9	0.2	46	3.04
1162776	Rock	2.50	0.020	2.5	4.5	4.8	90	<0.1	4.9	11.5	923	3.19	1.7	13.6	7.5	98	0.2	0.2	0.3	56	2.41
1162777	Rock	2.43	0.014	2.3	8.1	5.9	60	<0.1	5.5	11.3	805	2.92	2.0	11.6	8.5	127	0.1	0.3	0.3	48	2.35



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1162748	Rock	0.046	21	20	0.56	689	0.093	<20	1.00	0.043	0.63	1.5	0.01	3.2	0.2	0.15	5	<0.5	<0.2
1162749	Rock	0.037	16	20	0.62	917	0.114	<20	1.12	0.057	0.78	1.9	0.02	3.6	0.3	0.24	5	<0.5	<0.2
1162750	Rock	0.016	<1	<1	12.44	52	0.001	<20	0.04	0.001	0.02	<0.1	<0.01	0.7	<0.1	<0.05	<1	<0.5	<0.2
1162751	Rock	0.049	23	23	0.64	596	0.089	<20	0.94	0.058	0.68	1.7	0.04	5.2	0.3	0.23	6	<0.5	<0.2
1162752	Rock	0.045	18	22	0.54	1475	0.076	<20	0.79	0.046	0.52	1.8	0.04	4.7	0.2	0.18	5	<0.5	<0.2
1162753	Rock	0.068	5	54	1.19	889	0.127	<20	1.82	0.051	0.98	0.2	0.16	16.8	0.3	<0.05	6	<0.5	<0.2
1162754	Rock	0.024	2	13	0.42	289	0.045	<20	0.63	0.084	0.22	0.6	0.06	7.1	<0.1	<0.05	3	<0.5	<0.2
1162755	Rock	0.064	6	165	1.31	661	0.084	<20	1.77	0.066	0.98	<0.1	0.09	23.2	0.3	<0.05	6	<0.5	<0.2
1162756	Rock	0.073	8	81	0.73	2423	0.033	<20	1.30	0.032	0.67	0.5	0.15	23.2	0.3	0.05	4	<0.5	<0.2
1162757	Rock	0.078	8	83	0.85	1011	0.066	<20	1.34	0.056	0.72	0.2	0.09	22.4	0.2	<0.05	5	<0.5	<0.2
1162758	Rock	0.076	9	78	0.40	792	0.010	<20	0.90	0.024	0.41	0.2	0.19	29.0	0.1	<0.05	3	<0.5	<0.2
1162759	Rock	0.069	8	57	0.40	1175	0.014	<20	0.89	0.039	0.46	0.2	0.19	25.2	0.1	<0.05	4	<0.5	<0.2
1162760	Rock	0.070	8	54	0.37	1075	0.012	<20	0.80	0.030	0.42	0.2	0.18	24.8	0.1	<0.05	3	<0.5	<0.2
1162761	Rock	0.062	6	63	0.32	1285	0.016	<20	0.82	0.042	0.46	0.2	0.27	24.0	0.2	<0.05	4	<0.5	<0.2
1162762	Rock	0.026	4	51	0.25	653	0.004	<20	0.85	0.010	0.46	0.2	0.76	27.4	0.3	<0.05	4	<0.5	<0.2
1162763	Rock	0.048	3	20	0.28	815	0.016	<20	0.87	0.029	0.46	0.7	1.08	20.2	0.4	<0.05	4	<0.5	0.3
1162764	Rock	0.085	4	8	0.29	1083	0.032	<20	0.67	0.047	0.42	1.4	0.43	19.3	0.1	<0.05	3	<0.5	<0.2
1162765	Rock	0.071	3	6	0.15	878	0.023	<20	0.54	0.071	0.29	1.6	0.80	18.7	<0.1	<0.05	2	<0.5	<0.2
1162766	Rock	0.022	2	16	0.17	983	0.004	<20	0.46	0.021	0.22	0.4	0.91	18.1	0.1	<0.05	1	<0.5	0.2
1162767	Rock	0.005	1	29	0.68	1486	0.007	<20	0.85	0.017	0.51	0.1	0.72	16.6	0.2	<0.05	2	<0.5	<0.2
1162768	Rock	0.023	4	23	1.24	659	0.053	<20	0.89	0.034	0.68	0.4	0.26	18.4	0.2	<0.05	4	<0.5	<0.2
1162769	Rock	0.072	7	43	1.82	663	0.080	<20	1.40	0.046	0.92	0.3	0.12	19.0	0.3	<0.05	6	<0.5	<0.2
1162770	Rock Pulp	0.064	5	36	0.75	102	0.128	<20	1.54	0.085	0.13	10.0	0.05	5.1	<0.1	<0.05	5	<0.5	<0.2
1162771	Rock	0.064	5	57	2.39	391	0.122	<20	2.10	0.052	1.26	<0.1	0.03	16.9	0.3	<0.05	8	<0.5	<0.2
1162772	Rock	0.045	10	72	2.11	672	0.102	<20	1.68	0.052	1.22	0.1	0.11	17.7	0.4	<0.05	7	<0.5	<0.2
1162773	Rock	0.056	7	58	2.67	751	0.107	<20	1.87	0.023	1.19	<0.1	0.04	21.7	0.4	<0.05	7	<0.5	<0.2
1162774	Rock	0.034	4	44	1.86	483	0.087	<20	1.57	0.017	1.11	<0.1	0.32	21.4	0.4	<0.05	5	<0.5	0.4
1162775	Rock	0.030	5	28	1.00	1285	0.007	<20	0.70	0.013	0.38	0.4	0.35	9.1	0.1	<0.05	2	<0.5	<0.2
1162776	Rock	0.055	11	15	1.11	868	0.071	<20	1.06	0.026	0.81	0.6	0.22	8.6	0.2	<0.05	4	<0.5	<0.2
1162777	Rock	0.063	19	16	0.85	1078	0.046	<20	0.92	0.043	0.64	0.5	0.06	8.1	0.2	<0.05	4	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162778	Rock	3.07	0.341	2.9	15.9	7.3	74	1.8	7.7	9.8	597	2.79	2.4	311.0	9.4	73	0.1	0.3	0.1	46	1.18
1162779	Rock	2.51	0.025	2.1	8.0	10.6	46	0.1	7.3	7.8	796	2.15	1.6	17.2	10.2	1702	0.3	0.3	0.1	35	2.89
1162780	Rock	0.84	<0.005	0.1	1.4	1.4	12	<0.1	1.5	1.1	218	0.44	0.7	<0.5	0.2	45	<0.1	<0.1	<0.1	<2	18.91
1162781	Rock	2.86	0.013	2.1	10.4	20.9	44	0.1	7.4	8.8	644	2.68	1.8	8.7	11.0	168	0.1	0.4	0.3	42	2.01
1162782	Rock	2.75	0.015	2.1	6.9	4.2	41	<0.1	8.4	9.4	522	2.49	1.9	12.3	10.4	168	<0.1	0.3	0.1	45	1.39
1162783	Rock	2.05	0.112	3.7	12.4	20.6	52	0.6	6.9	7.2	848	2.33	1.7	103.7	10.9	220	0.3	0.4	0.2	42	2.51
1162784	Rock	2.01	<0.005	2.5	3.3	4.8	47	<0.1	7.9	7.7	1070	2.37	1.6	<0.5	10.0	173	0.2	0.2	0.1	45	2.84
1162785	Rock	1.98	<0.005	1.8	4.2	3.7	56	<0.1	6.8	11.8	1010	3.09	1.3	2.0	7.5	147	<0.1	0.2	0.1	55	3.08
1162786	Rock	2.09	0.104	1.4	12.7	5.0	86	0.6	3.0	17.2	1048	4.64	1.9	99.1	6.2	232	<0.1	0.2	0.1	146	2.80
1162787	Rock	2.81	0.225	1.9	6.3	4.7	69	1.0	5.6	13.8	815	3.43	1.2	163.3	8.7	117	<0.1	0.2	0.1	93	1.95
1162788	Rock	2.28	0.013	1.8	3.5	4.4	40	<0.1	6.0	8.6	532	2.38	2.4	8.5	7.5	195	<0.1	0.2	<0.1	35	1.99
1162789	Rock	2.27	0.013	2.1	6.5	7.5	72	<0.1	6.9	10.8	757	2.79	14.4	10.5	4.6	137	0.1	0.4	0.1	58	2.45
1162790	Rock	1.35	0.012	1.9	6.3	7.4	76	<0.1	7.5	11.4	785	2.89	12.3	8.8	4.9	140	0.1	0.4	0.2	62	2.36
1162791	Rock	2.67	<0.005	1.2	6.6	7.4	54	<0.1	6.9	10.9	956	2.73	1.8	0.7	7.0	162	0.2	0.4	0.3	49	3.20
1162792	Rock	3.23	<0.005	1.5	4.7	4.6	60	<0.1	7.5	10.1	784	2.96	1.7	1.2	8.8	142	0.1	0.2	0.2	43	2.14
1162793	Rock	2.28	<0.005	1.7	3.7	3.2	63	<0.1	8.4	13.7	1213	3.49	1.9	<0.5	8.6	69	<0.1	0.1	0.3	50	2.08
1162794	Rock	2.10	<0.005	1.7	5.1	3.3	75	<0.1	11.2	12.7	938	3.42	1.4	<0.5	7.8	70	<0.1	0.1	0.2	59	1.43
1162795	Rock	2.21	<0.005	1.5	4.7	3.6	65	<0.1	10.8	10.2	773	2.79	1.4	<0.5	9.8	77	<0.1	0.1	0.1	49	1.35
1162796	Rock	2.18	<0.005	2.0	3.7	2.6	36	<0.1	10.4	7.8	694	2.19	1.4	<0.5	10.9	53	<0.1	0.1	0.1	36	1.24
1162797	Rock	2.40	<0.005	2.2	4.0	2.7	38	<0.1	10.0	7.5	644	2.15	1.5	<0.5	11.6	69	<0.1	0.1	0.1	30	1.71
1162798	Rock	2.64	<0.005	2.3	4.7	2.8	34	<0.1	10.8	7.7	440	2.23	1.3	1.3	11.9	54	<0.1	<0.1	<0.1	38	1.01
1162799	Rock	2.07	<0.005	2.3	4.5	2.6	33	<0.1	9.8	7.4	536	1.95	1.7	1.0	9.3	52	<0.1	0.1	<0.1	30	1.23
1162800	Rock Pulp	0.13	2.269	69.6	2224.7	1359.7	3651	26.4	189.1	22.4	636	5.33	1211.3	1480.3	2.9	82	21.2	14.8	10.9	57	1.51
1162801	Rock	2.33	<0.005	2.7	6.4	2.6	51	<0.1	11.8	9.1	635	2.56	1.6	<0.5	9.0	54	<0.1	<0.1	<0.1	38	1.06
1162802	Rock	3.14	<0.005	2.3	3.2	3.0	32	<0.1	9.7	7.2	536	2.02	1.6	<0.5	10.3	63	<0.1	0.1	0.1	34	1.72
1162803	Rock	2.14	<0.005	2.3	3.8	3.8	44	<0.1	10.6	7.4	546	2.41	1.5	<0.5	10.5	62	0.1	0.2	0.1	60	1.97
1162804	Rock	2.43	<0.005	1.9	5.2	4.0	64	<0.1	10.2	8.0	611	2.54	1.1	<0.5	9.3	89	0.2	0.2	0.1	52	2.23
1162805	Rock	2.77	<0.005	1.7	3.9	3.1	41	<0.1	9.3	6.4	532	2.13	1.2	<0.5	10.4	73	<0.1	0.2	0.1	42	1.44
1162806	Rock	2.03	<0.005	1.8	4.1	3.0	67	<0.1	9.6	9.3	763	2.79	1.0	<0.5	9.2	91	0.1	0.1	0.1	57	2.18
1162807	Rock	2.71	<0.005	2.1	2.9	2.2	50	<0.1	9.8	7.8	667	2.42	1.0	<0.5	9.7	95	<0.1	<0.1	<0.1	47	1.63



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2		
1162778	Rock	0.058	21	19	0.79	749	0.084	<20	0.96	0.037	0.78	0.9	0.33	6.9	0.2	0.09	5	<0.5	1.2	
1162779	Rock	0.052	15	18	0.56	3560	0.031	<20	0.72	0.052	0.46	0.8	0.08	7.9	0.1	0.10	4	<0.5	<0.2	
1162780	Rock	0.017	<1	<1	10.82	56	0.002	<20	0.04	<0.001	0.03	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2	
1162781	Rock	0.054	23	22	0.84	853	0.075	<20	1.17	0.051	0.72	0.7	0.06	7.7	0.2	0.06	6	<0.5	<0.2	
1162782	Rock	0.056	26	25	0.87	724	0.109	<20	1.26	0.065	0.90	0.8	0.04	7.0	0.2	<0.05	7	<0.5	<0.2	
1162783	Rock	0.057	23	20	0.62	1966	0.060	<20	0.85	0.051	0.56	0.5	0.15	7.6	0.2	0.06	5	<0.5	0.4	
1162784	Rock	0.064	19	24	0.94	1271	0.092	<20	1.20	0.050	0.95	0.4	0.02	7.6	0.3	<0.05	6	<0.5	<0.2	
1162785	Rock	0.063	15	18	1.72	861	0.121	<20	1.79	0.024	1.50	0.2	0.02	9.3	0.4	<0.05	6	<0.5	<0.2	
1162786	Rock	0.095	16	9	1.93	1175	0.205	<20	2.36	0.032	1.88	0.3	0.09	14.8	0.4	0.18	9	<0.5	0.3	
1162787	Rock	0.060	20	18	1.39	1124	0.168	<20	1.74	0.043	1.34	0.5	0.16	11.5	0.3	<0.05	8	<0.5	0.5	
1162788	Rock	0.048	6	15	0.77	1838	0.024	<20	0.94	0.025	0.49	0.4	0.06	9.3	0.1	0.06	4	<0.5	<0.2	
1162789	Rock	0.038	4	22	1.07	1502	0.033	<20	1.06	0.007	0.61	0.3	0.14	12.2	0.2	0.15	4	<0.5	<0.2	
1162790	Rock	0.046	4	25	1.14	1393	0.043	<20	1.29	0.008	0.72	0.3	0.13	13.0	0.2	0.15	5	<0.5	<0.2	
1162791	Rock	0.051	8	23	1.25	695	0.095	<20	1.49	0.016	1.03	0.2	0.03	12.1	0.2	0.08	6	<0.5	<0.2	
1162792	Rock	0.052	15	24	1.10	1485	0.146	<20	1.66	0.041	1.23	0.3	0.02	10.0	0.3	<0.05	7	<0.5	<0.2	
1162793	Rock	0.062	20	38	1.53	644	0.201	<20	2.14	0.034	1.67	0.4	0.02	8.2	0.4	0.13	9	<0.5	<0.2	
1162794	Rock	0.057	21	76	1.49	750	0.204	<20	2.14	0.041	1.49	0.5	0.02	6.3	0.3	0.09	9	<0.5	<0.2	
1162795	Rock	0.058	24	61	1.21	689	0.143	<20	1.69	0.041	1.05	0.5	0.02	5.5	0.4	<0.05	8	<0.5	<0.2	
1162796	Rock	0.050	26	29	0.94	497	0.113	<20	1.37	0.058	0.77	0.6	0.03	5.0	0.3	0.09	8	<0.5	<0.2	
1162797	Rock	0.054	30	26	0.85	714	0.068	<20	1.21	0.045	0.52	0.7	0.02	4.8	0.2	0.05	7	<0.5	<0.2	
1162798	Rock	0.051	28	31	0.80	531	0.143	<20	1.30	0.067	0.89	0.7	0.03	5.5	0.3	<0.05	7	<0.5	<0.2	
1162799	Rock	0.048	23	26	0.86	480	0.109	<20	1.24	0.038	0.80	0.9	0.02	3.7	0.3	0.07	6	<0.5	<0.2	
1162800	Rock Pulp	0.063	12	47	0.89	213	0.100	<20	1.53	0.082	0.19	8.3	0.76	4.5	1.4	1.50	6	3.5	0.6	
1162801	Rock	0.063	21	33	1.08	598	0.145	<20	1.60	0.053	1.10	1.1	0.02	4.6	0.3	0.18	8	<0.5	<0.2	
1162802	Rock	0.055	26	27	0.84	658	0.100	<20	1.18	0.040	0.76	0.8	0.01	4.8	0.2	0.13	6	<0.5	<0.2	
1162803	Rock	0.054	32	49	1.01	443	0.127	<20	1.48	0.055	0.94	0.6	0.02	6.7	0.2	<0.05	7	<0.5	<0.2	
1162804	Rock	0.053	28	64	1.17	630	0.124	<20	1.55	0.049	0.91	0.7	0.01	6.3	0.2	<0.05	8	<0.5	<0.2	
1162805	Rock	0.053	27	42	0.96	520	0.122	<20	1.42	0.067	0.88	0.5	0.01	5.7	0.2	<0.05	7	<0.5	<0.2	
1162806	Rock	0.059	27	73	1.37	949	0.179	<20	1.84	0.043	1.23	0.7	0.01	6.7	0.3	0.06	9	<0.5	<0.2	
1162807	Rock	0.053	25	53	1.10	743	0.158	<20	1.59	0.061	1.03	0.6	0.02	6.2	0.2	0.09	8	<0.5	<0.2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162808	Rock	2.39	<0.005	1.8	3.7	1.9	69	<0.1	9.9	10.0	819	2.78	0.9	1.0	8.3	112	<0.1	0.1	<0.1	53	1.64
1162809	Rock	1.97	<0.005	1.7	3.2	2.7	48	<0.1	8.9	7.5	647	2.30	1.1	<0.5	11.3	83	<0.1	0.2	0.2	37	2.01
1162810	Rock Pulp	0.12	0.759	4.6	38.3	6.2	54	0.2	26.5	11.1	409	2.58	6.7	502.4	1.0	45	0.2	0.8	0.1	61	0.88
1162811	Rock	2.06	<0.005	1.9	3.4	2.3	33	<0.1	10.0	6.7	531	2.03	1.2	<0.5	11.0	64	<0.1	0.1	0.1	34	1.34
1162812	Rock	3.23	<0.005	1.6	3.3	2.3	32	<0.1	8.3	5.9	622	1.78	1.4	1.7	10.0	81	<0.1	0.2	0.1	28	1.92
1162813	Rock	2.68	<0.005	1.8	3.5	4.0	32	<0.1	8.4	6.1	597	2.02	2.0	1.0	12.2	101	<0.1	0.3	0.2	26	2.26
1162814	Rock	2.76	<0.005	2.0	3.1	3.0	31	<0.1	7.4	5.6	528	1.87	1.3	<0.5	12.6	98	<0.1	0.2	0.1	29	1.80
1162815	Rock	2.36	<0.005	2.3	5.5	2.8	34	<0.1	7.0	6.1	583	2.10	1.4	<0.5	12.5	87	<0.1	0.2	0.2	31	1.36
1162816	Rock	1.36	<0.005	2.8	9.6	2.1	34	<0.1	7.0	6.8	553	2.32	1.9	1.5	9.9	76	<0.1	0.3	0.1	29	0.86
1162817	Rock	1.34	<0.005	3.0	7.6	2.2	36	<0.1	6.8	6.5	566	2.27	2.2	1.2	9.2	72	<0.1	0.3	0.1	31	0.80
1162818	Rock	1.51	<0.005	3.5	6.6	2.3	35	<0.1	6.5	6.5	608	2.18	2.7	2.0	9.2	81	<0.1	0.4	0.1	28	1.06
1162819	Rock	1.99	<0.005	2.9	5.6	2.6	32	<0.1	6.2	5.9	645	2.08	2.1	63.4	9.2	97	<0.1	0.3	0.1	26	1.31
1162820	Rock	0.76	<0.005	<0.1	1.0	2.0	13	<0.1	0.6	0.6	194	0.39	4.3	0.9	<0.1	45	<0.1	0.3	<0.1	<2	19.59
1162821	Rock	1.74	<0.005	2.9	3.9	3.0	34	<0.1	6.5	6.0	770	2.20	1.6	1.4	11.2	132	<0.1	0.2	0.2	26	1.61
1162822	Rock	2.07	<0.005	2.7	3.5	7.8	28	<0.1	5.6	5.4	877	1.86	1.5	2.4	9.6	1321	<0.1	0.2	0.2	22	5.40
1162823	Rock	2.07	<0.005	2.4	5.4	4.3	32	<0.1	5.7	5.9	677	2.04	1.7	<0.5	12.9	382	<0.1	0.3	0.2	29	2.34
1162824	Rock	1.83	<0.005	2.4	3.7	4.5	38	<0.1	10.4	6.6	724	2.24	1.6	0.5	12.2	216	<0.1	0.3	0.2	32	2.08
1162825	Rock	1.91	<0.005	3.1	3.3	3.3	33	<0.1	9.1	6.2	584	1.95	1.3	<0.5	13.4	143	<0.1	0.2	0.1	27	1.58
1162826	Rock	1.94	<0.005	3.7	3.6	3.2	41	<0.1	11.7	7.8	632	2.38	1.1	<0.5	12.0	122	<0.1	0.2	0.1	39	1.34
1162827	Rock	2.24	<0.005	3.1	4.2	3.8	40	<0.1	9.7	7.2	638	2.16	1.2	<0.5	11.2	209	<0.1	0.2	0.1	34	1.68
1162828	Rock	2.18	<0.005	3.3	3.5	2.8	46	<0.1	10.2	7.8	641	2.27	1.2	<0.5	12.0	145	<0.1	0.2	0.1	37	1.53
1162829	Rock	2.44	<0.005	3.2	3.9	2.2	41	<0.1	8.9	7.7	708	2.26	0.9	0.6	12.0	124	<0.1	0.1	0.1	36	1.48
1162830	Rock	2.46	<0.005	3.4	3.8	2.3	40	<0.1	14.7	7.5	713	2.32	1.1	0.6	12.0	128	<0.1	0.1	0.1	37	1.49
1162831	Rock	2.38	<0.005	2.9	5.9	3.1	39	<0.1	9.5	6.5	727	2.16	1.6	0.5	11.0	200	<0.1	0.2	0.2	29	1.78
1162832	Rock	2.76	<0.005	2.7	5.0	2.6	38	<0.1	9.2	6.4	692	2.17	1.3	<0.5	9.6	140	<0.1	0.3	0.1	31	1.57
1162833	Rock	1.90	<0.005	2.3	11.7	4.6	40	<0.1	9.4	7.4	817	2.38	1.5	<0.5	10.5	209	<0.1	0.4	0.2	37	2.14
1162834	Rock	1.40	<0.005	2.2	4.2	2.6	42	<0.1	9.3	7.1	686	2.30	1.2	<0.5	11.7	130	<0.1	0.4	0.2	40	1.42
1162835	Rock	1.89	<0.005	2.0	3.4	2.9	41	<0.1	9.5	7.0	635	2.18	1.1	<0.5	11.5	130	<0.1	0.4	0.2	37	1.30
1162836	Rock	2.16	<0.005	2.3	2.9	3.8	44	<0.1	9.3	7.3	696	2.10	1.1	<0.5	14.2	190	<0.1	0.5	0.1	30	1.88
1162837	Rock	2.53	0.010	40.8	8.6	4.0	42	<0.1	8.8	7.1	734	2.17	1.5	4.3	11.0	204	0.1	0.9	0.2	33	2.09



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Ti ppm	S %	Ga ppm	Se ppm	Te ppm	
1162808	Rock	0.059	20	73	1.35	794	0.206	<20	1.82	0.049	1.32	0.8	0.01	6.3	0.3	0.12	8	<0.5	<0.2
1162809	Rock	0.048	33	38	0.89	599	0.127	<20	1.32	0.046	0.87	0.8	0.01	5.4	0.2	0.09	7	<0.5	<0.2
1162810	Rock Pulp	0.055	5	37	0.77	109	0.155	<20	1.60	0.088	0.13	10.4	0.04	5.8	<0.1	<0.05	5	<0.5	<0.2
1162811	Rock	0.047	28	30	0.80	493	0.124	<20	1.25	0.077	0.81	1.2	0.02	5.0	0.2	0.16	7	<0.5	<0.2
1162812	Rock	0.046	25	25	0.74	674	0.086	<20	1.01	0.046	0.65	0.9	0.03	4.3	0.2	0.14	5	<0.5	<0.2
1162813	Rock	0.046	29	23	0.68	582	0.038	<20	0.99	0.054	0.43	0.5	0.02	4.7	0.1	0.09	5	<0.5	<0.2
1162814	Rock	0.047	28	22	0.71	798	0.066	<20	0.98	0.054	0.49	0.8	0.05	5.3	0.1	0.06	5	<0.5	<0.2
1162815	Rock	0.046	28	24	0.70	557	0.088	<20	1.14	0.066	0.66	0.8	0.06	4.9	0.2	0.14	6	<0.5	<0.2
1162816	Rock	0.040	25	22	0.51	884	0.117	<20	0.98	0.043	0.61	0.3	0.05	4.2	0.2	0.06	5	<0.5	<0.2
1162817	Rock	0.039	24	24	0.51	820	0.133	<20	1.06	0.052	0.70	0.3	0.04	4.6	0.2	<0.05	5	<0.5	<0.2
1162818	Rock	0.039	25	24	0.46	745	0.101	<20	0.93	0.037	0.59	0.3	0.05	4.1	0.2	<0.05	4	<0.5	<0.2
1162819	Rock	0.036	24	23	0.47	898	0.100	<20	0.99	0.050	0.62	0.3	0.03	3.7	0.2	<0.05	5	<0.5	<0.2
1162820	Rock	0.014	<1	<1	11.11	33	<0.001	<20	0.02	<0.001	0.01	<0.1	<0.01	0.7	<0.1	<0.05	<1	<0.5	<0.2
1162821	Rock	0.038	27	21	0.51	1017	0.097	<20	1.06	0.051	0.64	0.6	0.03	4.2	0.2	0.07	5	<0.5	<0.2
1162822	Rock	0.035	24	19	0.46	2388	0.069	<20	0.91	0.038	0.52	0.8	0.02	3.6	0.2	0.10	4	<0.5	<0.2
1162823	Rock	0.040	29	19	0.51	1548	0.086	<20	0.89	0.038	0.55	1.3	<0.01	4.4	0.2	0.10	5	<0.5	<0.2
1162824	Rock	0.045	28	28	0.73	1046	0.093	<20	1.18	0.053	0.75	0.5	0.01	5.4	0.2	0.07	6	<0.5	<0.2
1162825	Rock	0.046	28	26	0.59	881	0.089	<20	0.97	0.050	0.62	0.7	0.02	4.8	0.2	0.06	5	<0.5	<0.2
1162826	Rock	0.050	28	35	0.80	730	0.142	<20	1.34	0.075	0.93	0.9	<0.01	5.9	0.3	0.06	8	<0.5	<0.2
1162827	Rock	0.050	26	30	0.72	1378	0.110	<20	1.16	0.045	0.75	0.8	0.01	4.8	0.2	0.08	6	<0.5	<0.2
1162828	Rock	0.045	29	33	0.75	908	0.133	<20	1.25	0.061	0.87	0.8	<0.01	6.0	0.2	0.07	7	<0.5	<0.2
1162829	Rock	0.051	29	33	0.73	1165	0.143	<20	1.23	0.051	0.87	1.2	0.01	5.2	0.3	0.09	6	<0.5	<0.2
1162830	Rock	0.048	30	43	0.74	1151	0.137	<20	1.29	0.066	0.89	1.2	0.02	5.2	0.3	0.09	7	<0.5	<0.2
1162831	Rock	0.046	28	26	0.59	1105	0.113	<20	1.02	0.038	0.68	1.2	0.01	4.2	0.2	0.09	6	<0.5	<0.2
1162832	Rock	0.040	25	27	0.60	965	0.101	<20	1.00	0.050	0.65	0.5	0.02	4.3	0.2	0.08	6	<0.5	<0.2
1162833	Rock	0.045	27	27	0.70	1056	0.082	<20	1.06	0.045	0.59	0.8	<0.01	4.9	0.2	0.11	6	<0.5	<0.2
1162834	Rock	0.046	28	29	0.80	918	0.128	<20	1.31	0.061	0.85	0.9	0.01	5.6	0.2	0.08	7	<0.5	<0.2
1162835	Rock	0.043	28	27	0.79	892	0.108	<20	1.21	0.053	0.78	0.8	0.03	5.5	0.2	0.10	7	<0.5	<0.2
1162836	Rock	0.044	30	27	0.71	1398	0.072	<20	1.05	0.064	0.52	0.9	0.09	5.8	0.2	0.09	6	<0.5	<0.2
1162837	Rock	0.042	25	27	0.72	1395	0.050	<20	0.94	0.052	0.36	1.1	0.10	5.7	0.1	0.13	6	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1162838	Rock	2.71	<0.005	4.7	3.9	2.4	41	<0.1	8.4	6.4	757	2.55	1.0	0.7	10.5	176	<0.1	0.8	0.3	45	1.54
1162839	Rock	2.37	<0.005	3.7	3.9	2.3	50	<0.1	9.2	8.0	868	2.73	1.1	<0.5	10.5	162	<0.1	0.6	0.2	48	1.70
1162840	Rock Pulp	0.12	2.011	67.1	2193.2	1363.6	3573	26.5	185.7	21.2	643	5.24	1199.8	723.9	2.7	77	21.9	14.5	9.8	56	1.51
1162841	Rock	1.84	<0.005	3.4	3.8	2.2	36	<0.1	7.7	6.7	776	2.41	1.1	1.1	11.2	121	<0.1	0.5	0.2	43	1.66
1162842	Rock	2.79	<0.005	2.8	5.5	4.1	38	<0.1	5.4	4.6	652	1.86	2.0	0.7	7.6	187	<0.1	0.9	0.2	32	2.11
1162843	Rock	2.74	<0.005	3.2	5.8	6.3	35	<0.1	4.5	3.6	579	1.59	2.3	<0.5	7.1	262	<0.1	1.0	0.1	26	1.98
1162844	Rock	2.82	<0.005	30.8	6.5	4.5	33	<0.1	6.9	6.5	566	2.18	1.7	2.5	9.3	539	<0.1	0.8	0.6	27	1.68
1162845	Rock	2.26	<0.005	5.3	9.3	3.5	43	<0.1	8.8	9.0	586	2.83	1.1	<0.5	11.2	269	<0.1	0.8	0.4	39	1.64
1162846	Rock	3.13	<0.005	4.4	8.0	3.6	39	<0.1	5.7	4.7	513	1.88	1.5	0.6	7.6	226	<0.1	0.8	0.1	39	1.38
1162847	Rock	1.40	<0.005	4.5	7.2	3.4	36	<0.1	6.6	5.9	583	2.19	5.6	0.5	8.7	197	<0.1	0.7	0.2	36	1.49
1162848	Rock	2.37	<0.005	3.2	6.8	3.8	43	<0.1	8.4	8.2	558	2.61	1.7	<0.5	9.3	1595	<0.1	0.4	0.2	33	1.93
1162849	Rock	2.33	<0.005	3.4	5.7	3.7	34	<0.1	7.9	9.3	580	2.79	3.6	0.8	10.9	287	<0.1	0.6	0.3	33	2.00
1162850	Rock	0.54	<0.005	0.1	1.1	1.1	10	<0.1	1.6	0.8	210	0.45	<0.5	1.6	0.1	48	<0.1	<0.1	<0.1	<2	19.25
1162851	Rock	2.36	<0.005	3.7	6.4	2.1	35	<0.1	8.5	9.7	600	2.72	2.2	0.6	9.9	276	<0.1	0.4	0.2	38	1.78
1162852	Rock	3.03	<0.005	8.3	13.6	5.4	50	<0.1	8.7	10.0	605	2.98	0.8	1.2	11.1	1357	0.1	0.3	0.2	50	1.87
1162853	Rock	2.26	<0.005	4.3	5.3	2.2	37	<0.1	10.0	9.8	624	3.05	0.9	0.6	9.7	299	<0.1	0.2	0.5	42	1.40
1162854	Rock	2.03	<0.005	4.4	9.1	2.0	38	<0.1	9.9	9.2	579	2.82	9.8	0.8	8.2	399	<0.1	0.3	1.2	41	1.10
1162855	Rock	2.39	<0.005	4.1	7.7	1.3	28	<0.1	10.1	7.2	503	2.45	2.3	<0.5	7.6	319	<0.1	0.3	0.6	38	1.42



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000285.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1162838	Rock	0.048	27	28	0.91	1130	0.125	<20	1.40	0.068	0.89	1.0	0.03	5.3	0.2	0.10	7	<0.5	<0.2
1162839	Rock	0.049	26	28	1.04	1148	0.134	<20	1.48	0.051	0.98	1.0	0.02	5.8	0.2	0.12	7	<0.5	<0.2
1162840	Rock Pulp	0.064	12	45	0.85	165	0.093	<20	1.50	0.084	0.19	7.8	0.77	4.0	1.3	1.48	6	3.6	0.5
1162841	Rock	0.045	25	29	0.83	545	0.121	<20	1.28	0.064	0.89	1.3	0.01	6.5	0.2	0.10	7	<0.5	<0.2
1162842	Rock	0.033	12	19	0.51	807	0.033	<20	0.76	0.045	0.41	0.7	0.03	4.8	0.1	0.07	4	<0.5	<0.2
1162843	Rock	0.024	8	16	0.44	1393	0.021	<20	0.66	0.038	0.39	0.6	0.04	4.1	0.1	0.07	3	<0.5	<0.2
1162844	Rock	0.041	16	36	0.68	712	0.051	<20	1.09	0.029	0.76	0.4	0.09	7.5	0.3	0.16	5	<0.5	<0.2
1162845	Rock	0.051	29	61	0.98	1270	0.122	<20	1.34	0.044	1.06	1.0	0.09	7.3	0.4	0.21	6	<0.5	<0.2
1162846	Rock	0.032	19	36	0.50	1378	0.068	<20	0.77	0.060	0.55	1.3	0.03	3.6	0.2	0.15	4	<0.5	<0.2
1162847	Rock	0.037	22	42	0.68	1588	0.080	<20	0.95	0.049	0.68	1.2	0.05	4.4	0.2	0.18	5	<0.5	<0.2
1162848	Rock	0.047	27	59	0.91	2120	0.129	<20	1.38	0.057	1.04	1.1	0.05	5.6	0.3	0.18	6	<0.5	<0.2
1162849	Rock	0.050	27	61	0.98	1159	0.119	<20	1.37	0.049	0.94	0.9	0.10	8.1	0.3	0.17	7	<0.5	<0.2
1162850	Rock	0.014	<1	<1	12.11	24	0.001	<20	0.03	0.002	0.02	<0.1	<0.01	0.7	<0.1	<0.05	<1	<0.5	<0.2
1162851	Rock	0.055	28	72	1.15	869	0.140	<20	1.47	0.060	1.13	1.3	0.08	6.9	0.3	0.16	8	<0.5	<0.2
1162852	Rock	0.052	29	75	1.05	906	0.120	<20	1.24	0.073	0.75	1.3	0.04	8.4	0.2	0.33	7	<0.5	<0.2
1162853	Rock	0.058	28	80	1.24	950	0.170	<20	1.77	0.067	1.31	0.7	0.11	5.7	0.3	0.12	8	<0.5	0.2
1162854	Rock	0.049	22	67	1.09	711	0.166	<20	1.53	0.060	1.14	1.7	0.07	5.0	0.3	0.24	7	<0.5	0.8
1162855	Rock	0.058	19	73	0.98	543	0.154	<20	1.22	0.103	0.77	1.9	0.05	6.8	0.2	0.17	6	<0.5	0.3



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 1 of 3 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000285.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1162726	Rock	2.04	<0.005	1.8	84.5	4.8	86	0.1	13.1	21.8	1081	4.92	1.0	<0.5	3.0	147	0.2	2.0	<0.1	148	3.63
REP 1162726	QC	<0.005																			
1162740	Rock Pulp	0.12	2.014	62.1	2192.1	1387.2	3579	26.7	183.3	19.3	650	5.37	1185.3	705.5	2.9	80	22.2	15.7	10.0	57	1.54
REP 1162740	QC	2.155																			
1162748	Rock	2.13	<0.005	2.5	4.7	1.8	32	<0.1	6.1	4.7	590	1.86	0.7	<0.5	8.0	557	<0.1	0.1	0.1	23	1.06
REP 1162748	QC	2.7 4.6 1.8 33 <0.1 6.1 4.8 596 1.89 0.6 <0.5 8.0 544 <0.1 <0.1 0.1 23 1.07																			
1162764	Rock	2.07	0.041	2.7	79.9	2.9	111	0.2	3.0	14.0	953	4.20	12.2	35.3	0.8	59	0.4	1.3	<0.1	98	0.21
REP 1162764	QC	2.6 77.6 2.7 106 0.2 3.0 13.6 926 4.09 11.9 32.2 0.7 56 0.4 1.3 <0.1 97 0.20																			
REP 1162773	QC	0.007																			
1162799	Rock	2.07	<0.005	2.3	4.5	2.6	33	<0.1	9.8	7.4	536	1.95	1.7	1.0	9.3	52	<0.1	0.1	<0.1	30	1.23
REP 1162799	QC	2.4 4.1 2.6 32 <0.1 9.4 7.1 543 1.95 1.7 0.9 9.1 53 <0.1 <0.1 <0.1 30 1.24																			
1162801	Rock	2.33	<0.005	2.7	6.4	2.6	51	<0.1	11.8	9.1	635	2.56	1.6	<0.5	9.0	54	<0.1	<0.1	<0.1	38	1.06
REP 1162801	QC	<0.005																			
1162834	Rock	1.40	<0.005	2.2	4.2	2.6	42	<0.1	9.3	7.1	686	2.30	1.2	<0.5	11.7	130	<0.1	0.4	0.2	40	1.42
REP 1162834	QC	2.2 4.1 2.7 42 <0.1 9.7 6.5 696 2.33 1.1 <0.5 11.7 130 <0.1 0.4 0.2 40 1.44																			
1162846	Rock	3.13	<0.005	4.4	8.0	3.6	39	<0.1	5.7	4.7	513	1.88	1.5	0.6	7.6	226	<0.1	0.8	0.1	39	1.38
REP 1162846	QC	<0.005																			
Core Reject Duplicates																					
1162739	Rock	1.93	0.402	2.8	12.3	12.2	62	2.3	7.7	7.5	751	2.49	0.6	417.7	10.0	159	0.2	0.4	0.1	44	2.27
DUP 1162739	QC	0.367 2.3 12.2 11.5 60 2.1 7.1 6.9 742 2.39 0.6 346.1 9.4 160 0.1 0.4 0.1 43 2.27																			
1162773	Rock	2.18	0.006	1.1	16.1	2.6	81	<0.1	20.4	24.6	1192	5.01	1.9	3.3	1.1	181	<0.1	0.3	<0.1	131	3.88
DUP 1162773	QC	0.008 1.0 15.5 2.6 80 <0.1 20.5 24.2 1178 4.95 1.6 2.2 1.0 176 <0.1 0.3 <0.1 128 3.94																			
1162807	Rock	2.71	<0.005	2.1	2.9	2.2	50	<0.1	9.8	7.8	667	2.42	1.0	<0.5	9.7	95	<0.1	<0.1	<0.1	47	1.63
DUP 1162807	QC	<0.005 1.9 3.4 2.2 54 <0.1 9.7 8.7 686 2.48 0.9 1.1 9.7 94 <0.1 0.1 0.1 48 1.67																			
1162841	Rock	1.84	<0.005	3.4	3.8	2.2	36	<0.1	7.7	6.7	776	2.41	1.1	1.1	11.2	121	<0.1	0.5	0.2	43	1.66
DUP 1162841	QC	<0.005 3.5 3.7 2.1 38 <0.1 8.2 7.6 770 2.38 0.9 1.9 11.7 120 <0.1 0.5 0.2 43 1.63																			
Reference Materials																					
STD DS10	Standard	14.5 158.8 147.2 354 2.1 74.9 14.4 876 2.71 48.2 68.8 7.7 67 2.5 7.8 12.5 43 1.05																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 1 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000285.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1162726	Rock	0.039	7	50	2.19	665	0.082	<20	1.52	0.070	1.05	<0.1	0.32	21.4	0.3	0.13	7	<0.5	<0.2
REP 1162726	QC																		
1162740	Rock Pulp	0.061	12	46	0.85	207	0.094	<20	1.50	0.084	0.19	8.2	0.74	4.3	1.3	1.50	6	3.6	0.6
REP 1162740	QC																		
1162748	Rock	0.046	21	20	0.56	689	0.093	<20	1.00	0.043	0.63	1.5	0.01	3.2	0.2	0.15	5	<0.5	<0.2
REP 1162748	QC	0.045	21	20	0.56	686	0.095	<20	1.01	0.044	0.63	1.4	<0.01	3.4	0.2	0.15	5	<0.5	<0.2
1162764	Rock	0.085	4	8	0.29	1083	0.032	<20	0.67	0.047	0.42	1.4	0.43	19.3	0.1	<0.05	3	<0.5	<0.2
REP 1162764	QC	0.084	4	8	0.29	1047	0.032	<20	0.65	0.046	0.41	1.3	0.41	18.6	0.1	<0.05	3	<0.5	<0.2
REP 1162773	QC																		
1162799	Rock	0.048	23	26	0.86	480	0.109	<20	1.24	0.038	0.80	0.9	0.02	3.7	0.3	0.07	6	<0.5	<0.2
REP 1162799	QC	0.050	21	24	0.86	448	0.112	<20	1.25	0.039	0.81	0.8	0.02	3.6	0.3	0.07	6	<0.5	<0.2
1162801	Rock	0.063	21	33	1.08	598	0.145	<20	1.60	0.053	1.10	1.1	0.02	4.6	0.3	0.18	8	<0.5	<0.2
REP 1162801	QC																		
1162834	Rock	0.046	28	29	0.80	918	0.128	<20	1.31	0.061	0.85	0.9	0.01	5.6	0.2	0.08	7	<0.5	<0.2
REP 1162834	QC	0.050	28	27	0.80	939	0.127	<20	1.31	0.061	0.86	0.9	0.02	5.5	0.3	0.08	7	<0.5	<0.2
1162846	Rock	0.032	19	36	0.50	1378	0.068	<20	0.77	0.060	0.55	1.3	0.03	3.6	0.2	0.15	4	<0.5	<0.2
REP 1162846	QC																		
Core Reject Duplicates																			
1162739	Rock	0.046	16	22	0.79	973	0.035	<20	0.71	0.065	0.48	0.8	0.26	7.5	0.1	0.35	3	<0.5	1.4
DUP 1162739	QC	0.044	15	20	0.78	1096	0.034	<20	0.70	0.065	0.48	0.8	0.22	7.3	0.1	0.34	4	<0.5	1.3
1162773	Rock	0.056	7	58	2.67	751	0.107	<20	1.87	0.023	1.19	<0.1	0.04	21.7	0.4	<0.05	7	<0.5	<0.2
DUP 1162773	QC	0.060	7	58	2.67	709	0.107	<20	1.82	0.023	1.18	<0.1	0.05	21.1	0.3	<0.05	7	<0.5	<0.2
1162807	Rock	0.053	25	53	1.10	743	0.158	<20	1.59	0.061	1.03	0.6	0.02	6.2	0.2	0.09	8	<0.5	<0.2
DUP 1162807	QC	0.052	26	54	1.13	764	0.158	<20	1.63	0.064	1.05	0.7	0.02	6.4	0.2	0.10	8	<0.5	<0.2
1162841	Rock	0.045	25	29	0.83	545	0.121	<20	1.28	0.064	0.89	1.3	0.01	6.5	0.2	0.10	7	<0.5	<0.2
DUP 1162841	QC	0.045	25	27	0.82	538	0.119	<20	1.27	0.064	0.88	1.2	0.01	6.4	0.3	0.11	7	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.073	19	58	0.78	424	0.086	<20	1.03	0.068	0.34	2.8	0.26	3.3	4.9	0.28	4	2.4	4.8



QUALITY CONTROL REPORT

WHI16000285.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			15.0	165.5	155.2	354	1.8	78.7	13.6	903	2.79	47.6	60.8	7.9	67	2.9	7.6	12.5	44	1.07
STD DS10	Standard			15.0	170.4	161.7	367	1.9	82.1	14.2	921	2.84	50.1	69.0	8.5	71	3.1	8.1	12.7	45	1.10
STD DS10	Standard			14.3	153.6	150.6	359	1.9	75.0	14.4	887	2.71	50.6	72.8	7.6	67	2.9	7.6	12.8	42	1.07
STD OREAS45EA	Standard			1.6	736.7	15.5	33	0.3	418.6	59.8	419	23.26	12.4	52.2	10.9	4	<0.1	0.2	0.3	323	0.04
STD OREAS45EA	Standard			1.5	715.6	14.3	29	0.3	378.2	49.7	396	20.89	11.0	50.0	10.1	4	<0.1	0.3	0.2	290	0.03
STD OREAS45EA	Standard			1.5	751.7	15.3	31	0.3	407.4	56.4	418	22.89	10.9	50.7	10.7	4	<0.1	0.3	0.3	305	0.03
STD OREAS45EA	Standard			1.5	709.9	15.5	33	0.3	394.7	57.3	410	22.52	11.8	59.2	10.4	4	<0.1	0.3	0.3	308	0.04
STD OXD108	Standard		0.414																		
STD OXD108	Standard		0.416																		
STD OXD108	Standard		0.422																		
STD OXD108	Standard		0.405																		
STD OXI121	Standard		1.801																		
STD OXI121	Standard		1.823																		
STD OXI121	Standard		1.782																		
STD OXI121	Standard		1.809																		
STD OXN117	Standard		7.312																		
STD OXN117	Standard		7.571																		
STD OXN117	Standard		7.649																		
STD OXN117	Standard		7.640																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		



QUALITY CONTROL REPORT

WHI16000285.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
STD DS10	Standard	0.070	19	58	0.78	438	0.088	<20	1.06	0.074	0.34	2.7	0.31	2.9	5.4	0.28	5	2.0	4.9
STD DS10	Standard	0.082	20	62	0.80	457	0.088	<20	1.08	0.075	0.35	2.7	0.30	3.1	5.4	0.29	5	2.4	5.0
STD DS10	Standard	0.087	19	60	0.79	429	0.085	<20	1.05	0.071	0.34	2.8	0.28	3.1	5.4	0.28	4	2.2	4.9
STD OREAS45EA	Standard	0.027	9	915	0.10	164	0.107	<20	3.50	0.015	0.06	<0.1	<0.01	82.5	<0.1	<0.05	13	1.6	<0.2
STD OREAS45EA	Standard	0.026	7	819	0.08	148	0.094	<20	3.32	0.024	0.05	<0.1	0.01	73.0	<0.1	<0.05	12	0.9	<0.2
STD OREAS45EA	Standard	0.027	8	871	0.09	154	0.102	<20	3.46	0.027	0.06	<0.1	<0.01	77.5	<0.1	<0.05	13	0.9	<0.2
STD OREAS45EA	Standard	0.035	8	889	0.10	164	0.108	<20	3.35	0.016	0.05	<0.1	<0.01	72.6	<0.1	<0.05	13	1.1	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT **WHI16000285.1**

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
BLK	Blank	<0.005																				
Prep Wash																						
ROCK-WHI	Prep Blank	<0.005	3.0	4.2	4.2	32	<0.1	1.4	3.9	427	1.73	2.0	<0.5	2.6	28	<0.1	0.1	<0.1	24	0.65		
ROCK-WHI	Prep Blank	<0.005	1.0	3.6	2.9	29	<0.1	1.4	3.8	440	1.79	1.4	<0.5	2.7	33	<0.1	<0.1	<0.1	24	0.61		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000285.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.044	5	3	0.39	72	0.098	<20	0.99	0.116	0.11	0.1	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.041	6	3	0.40	87	0.099	<20	0.96	0.124	0.11	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 19, 2016
Report Date: October 05, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000286.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-09-09-Rock-RAB
P.O. Number
Number of Samples: 140

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	139	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	139	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	139	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162856	Rock	1.47	0.009	1.4	42.5	21.3	62	<0.1	31.0	14.9	608	3.04	22.7	6.7	5.2	57	0.2	1.2	0.2	66	1.08
1162857	Rock	1.92	0.117	1.3	104.1	21.9	68	0.2	22.9	22.1	594	4.05	30.5	84.7	0.9	32	0.2	1.5	0.1	114	0.46
1162858	Rock	1.87	0.459	1.3	67.6	11.1	85	0.4	17.7	22.4	730	4.05	38.1	299.5	1.4	32	0.3	1.0	<0.1	106	0.20
1162859	Rock	2.61	0.019	0.9	91.3	7.8	117	0.2	22.5	24.9	947	4.75	42.9	14.2	1.1	31	0.2	1.1	<0.1	138	0.28
1162860	Rock	2.85	0.018	1.0	94.4	7.6	115	0.2	23.4	24.9	974	4.75	45.9	14.8	1.1	31	0.3	1.1	<0.1	138	0.27
1162861	Rock	1.49	0.009	1.6	116.7	13.1	107	0.1	18.9	25.3	831	5.08	48.9	7.2	0.9	25	0.4	1.1	<0.1	166	0.24
1162862	Rock	1.58	0.021	2.9	134.6	13.0	87	0.1	16.0	26.0	693	4.87	58.9	18.6	1.2	24	0.3	0.7	0.1	173	0.21
1162863	Rock	1.51	0.029	1.9	128.1	11.1	109	0.1	20.0	22.0	689	5.22	38.0	15.1	1.1	29	0.3	1.3	0.1	158	0.22
1162864	Rock	1.75	0.209	1.3	115.9	6.9	53	0.3	11.4	13.8	603	2.82	18.0	210.9	1.4	23	0.2	0.4	0.1	74	0.14
1162865	Rock	1.59	0.018	1.0	192.9	3.7	112	0.1	28.3	29.3	1053	5.28	29.3	9.7	0.8	27	0.3	1.5	<0.1	177	0.26
1162866	Rock	1.25	0.021	1.4	193.7	4.5	164	0.2	90.7	43.0	1480	5.91	39.1	46.6	0.5	25	0.5	1.2	<0.1	191	0.22
1162867	Rock	1.30	0.027	1.3	194.4	4.9	129	0.2	52.4	28.5	1273	5.16	50.3	23.2	0.4	29	0.5	1.1	<0.1	149	0.17
1162868	Rock	1.52	0.110	2.3	218.8	12.0	63	0.2	28.3	21.8	871	3.66	22.6	120.7	0.5	33	0.4	1.8	0.1	54	0.11
1162869	Rock	1.57	0.007	1.7	65.2	7.0	63	<0.1	29.8	23.7	825	3.81	11.1	5.9	0.4	41	0.1	1.5	<0.1	47	1.97
1162870	Rock Pulp	0.12	0.821	4.5	35.5	5.5	52	0.3	24.9	10.7	387	2.48	7.0	969.1	1.0	37	0.2	0.8	0.1	58	0.75
1162871	Rock	1.65	<0.005	2.0	127.3	6.5	58	<0.1	58.4	41.0	990	4.67	37.3	3.6	0.3	47	<0.1	0.5	<0.1	78	3.94
1162872	Rock	1.82	<0.005	0.4	95.4	3.7	51	<0.1	47.7	30.8	885	4.32	7.1	1.2	0.3	81	0.1	0.5	<0.1	82	4.53
1162873	Rock	1.67	<0.005	0.5	91.4	2.1	51	<0.1	45.0	28.1	994	4.37	1.8	2.0	0.3	200	0.1	0.7	<0.1	96	3.91
1162874	Rock	1.99	0.008	1.2	80.2	4.2	49	<0.1	29.8	21.8	774	3.58	5.5	5.5	3.1	96	0.2	0.7	<0.1	78	3.29
1162875	Rock	1.78	<0.005	1.7	52.2	8.7	56	<0.1	18.7	14.0	973	3.01	3.2	3.6	4.5	98	0.3	0.4	0.1	43	5.00
1162876	Rock	1.95	<0.005	1.8	33.4	4.7	66	<0.1	30.9	17.3	1205	3.48	1.8	2.0	2.6	146	0.1	0.3	<0.1	66	5.28
1162877	Rock	1.78	0.007	1.5	65.2	3.9	72	<0.1	36.0	22.5	1286	4.42	1.4	5.8	1.0	99	0.1	0.7	<0.1	95	6.23
1162878	Rock	1.96	0.007	1.4	69.1	3.6	66	<0.1	42.2	25.1	1552	4.56	1.7	3.5	1.6	126	0.2	0.7	<0.1	106	6.47
1162879	Rock	1.87	0.021	1.1	42.9	3.0	87	<0.1	86.6	30.6	1176	4.40	1.7	14.3	1.5	135	0.3	0.3	<0.1	140	4.82
1162880	Rock	0.63	<0.005	<0.1	0.8	1.2	14	<0.1	1.5	1.3	240	0.41	<0.5	<0.5	<0.1	47	<0.1	<0.1	<0.1	<2	19.64
1162881	Rock	2.15	<0.005	0.8	80.6	2.9	80	<0.1	29.5	29.4	1031	5.06	1.4	2.3	1.2	200	0.3	0.1	<0.1	177	4.64
1162882	Rock	2.04	<0.005	1.1	18.5	2.0	70	<0.1	17.1	20.6	890	4.12	3.2	1.2	1.2	102	0.2	0.1	<0.1	130	2.90
1162883	Rock	2.05	<0.005	1.2	19.9	2.6	72	<0.1	11.7	18.8	583	4.06	1.7	0.8	0.8	39	<0.1	0.1	<0.1	92	1.08
1162884	Rock	1.88	<0.005	1.0	15.3	1.9	70	<0.1	9.8	19.8	554	3.98	1.4	0.6	0.7	43	<0.1	0.2	<0.1	93	1.03
1162885	Rock	2.12	<0.005	1.7	59.7	2.9	75	<0.1	13.4	19.3	675	3.77	3.1	3.1	1.2	85	<0.1	0.2	<0.1	120	2.23



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1162856	Rock	0.067	16	55	0.83	2273	0.090	<20	1.20	0.044	0.49	0.5	0.19	9.4	0.2	0.05	5	<0.5	<0.2
1162857	Rock	0.090	3	40	0.65	2113	0.071	<20	1.10	0.056	0.48	0.2	0.33	14.0	0.1	<0.05	4	<0.5	0.3
1162858	Rock	0.063	4	46	0.37	2628	0.018	<20	0.84	0.051	0.42	0.1	0.39	17.5	0.1	0.06	3	<0.5	0.8
1162859	Rock	0.089	5	42	0.57	1896	0.026	<20	1.14	0.029	0.67	0.3	0.16	22.7	0.2	<0.05	6	<0.5	<0.2
1162860	Rock	0.089	5	44	0.57	2096	0.027	<20	1.12	0.027	0.67	0.3	0.18	22.9	0.2	<0.05	5	<0.5	<0.2
1162861	Rock	0.097	4	38	0.29	1306	0.010	<20	0.84	0.031	0.48	0.2	0.19	23.1	0.1	<0.05	4	<0.5	<0.2
1162862	Rock	0.098	5	39	0.25	257	0.011	<20	0.74	0.041	0.43	0.2	0.21	22.4	0.1	<0.05	4	0.6	<0.2
1162863	Rock	0.087	4	38	0.53	1580	0.027	<20	1.18	0.030	0.73	0.1	0.16	22.6	0.2	<0.05	4	<0.5	<0.2
1162864	Rock	0.044	4	29	0.24	2029	0.017	<20	0.55	0.066	0.29	0.3	0.19	11.3	0.1	<0.05	2	<0.5	0.5
1162865	Rock	0.088	4	35	0.75	1303	0.045	<20	1.27	0.028	0.89	0.6	0.15	26.9	0.3	<0.05	6	<0.5	<0.2
1162866	Rock	0.062	3	223	1.39	522	0.067	<20	1.77	0.023	1.55	0.3	0.22	40.4	0.6	<0.05	8	<0.5	<0.2
1162867	Rock	0.046	2	86	0.64	425	0.018	<20	1.16	0.018	0.80	0.3	0.43	32.2	0.3	<0.05	4	<0.5	<0.2
1162868	Rock	0.019	1	27	0.21	1314	0.001	<20	0.59	0.019	0.22	0.1	0.79	13.9	0.2	<0.05	2	<0.5	0.3
1162869	Rock	0.036	1	24	0.26	523	<0.001	<20	0.62	0.003	0.33	<0.1	0.64	13.9	0.2	<0.05	1	<0.5	<0.2
1162870	Rock Pulp	0.062	4	33	0.70	107	0.118	<20	1.40	0.078	0.13	11.1	0.07	5.0	<0.1	<0.05	5	<0.5	<0.2
1162871	Rock	0.043	2	45	0.50	311	<0.001	<20	0.90	0.008	0.36	<0.1	0.60	23.0	0.3	<0.05	1	<0.5	<0.2
1162872	Rock	0.041	2	43	1.13	820	0.002	<20	0.79	0.011	0.40	<0.1	0.35	22.1	0.1	<0.05	2	<0.5	<0.2
1162873	Rock	0.038	3	73	2.04	3885	0.015	<20	1.31	0.033	0.52	<0.1	0.07	23.3	0.1	0.09	4	<0.5	<0.2
1162874	Rock	0.040	10	45	1.42	931	0.012	<20	0.86	0.040	0.32	<0.1	0.14	18.1	<0.1	<0.05	4	<0.5	<0.2
1162875	Rock	0.056	14	22	1.46	1161	0.008	<20	0.84	0.016	0.42	<0.1	0.12	8.7	0.1	<0.05	3	<0.5	<0.2
1162876	Rock	0.064	9	51	1.44	2145	0.009	<20	0.71	0.028	0.27	0.3	0.13	15.4	<0.1	<0.05	4	<0.5	<0.2
1162877	Rock	0.063	8	50	1.87	1630	0.032	<20	1.44	0.024	0.46	0.2	0.04	17.2	<0.1	<0.05	6	<0.5	<0.2
1162878	Rock	0.055	10	97	2.73	1781	0.032	<20	1.30	0.024	0.30	0.1	0.07	19.4	<0.1	<0.05	6	<0.5	<0.2
1162879	Rock	0.052	8	227	3.02	1314	0.072	<20	1.90	0.028	0.64	<0.1	0.38	22.6	0.2	<0.05	8	<0.5	0.3
1162880	Rock	0.018	<1	<1	11.37	25	<0.001	<20	0.03	<0.001	0.01	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1162881	Rock	0.062	6	92	2.90	594	0.154	<20	2.40	0.030	1.25	0.1	0.24	23.7	0.3	<0.05	11	<0.5	<0.2
1162882	Rock	0.055	6	115	2.50	355	0.158	<20	2.25	0.044	1.23	0.2	0.03	15.7	0.2	<0.05	9	<0.5	<0.2
1162883	Rock	0.063	4	45	2.33	520	0.241	<20	2.43	0.059	1.03	0.1	0.03	8.2	0.2	<0.05	10	<0.5	<0.2
1162884	Rock	0.064	4	52	2.59	589	0.240	<20	2.76	0.045	1.50	0.1	0.02	8.4	0.3	<0.05	9	<0.5	<0.2
1162885	Rock	0.073	7	83	1.55	148	0.185	<20	1.58	0.072	0.76	0.2	0.03	10.2	0.2	<0.05	8	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162886	Rock	2.07	<0.005	1.4	56.6	1.9	92	<0.1	29.1	24.1	1039	4.40	5.2	1.9	0.7	96	0.1	0.3	<0.1	113	3.35
1162887	Rock	2.04	<0.005	1.1	58.0	2.3	78	<0.1	18.4	22.4	954	4.52	1.2	3.9	1.1	126	0.1	0.3	<0.1	121	3.79
1162888	Rock	1.72	0.006	2.3	32.8	3.1	78	<0.1	22.0	20.0	895	4.04	1.9	11.8	2.3	135	0.2	0.5	<0.1	127	2.92
1162889	Rock	1.57	0.031	1.9	32.4	12.2	91	0.2	26.2	21.7	1233	4.63	1.7	29.8	1.3	249	0.2	0.5	0.1	118	5.61
1162890	Rock	1.45	0.046	1.8	33.4	12.0	88	0.2	24.6	21.0	1207	4.62	1.7	42.9	1.2	223	0.2	0.5	0.1	119	5.67
1162891	Rock	1.97	0.069	1.1	32.9	3.2	69	0.4	26.8	20.2	871	4.75	1.6	63.5	2.1	250	<0.1	0.6	<0.1	123	2.74
1162892	Rock	1.84	0.086	2.3	18.2	4.4	80	0.4	23.4	17.6	917	4.25	1.2	80.6	4.6	265	0.2	0.3	0.1	114	3.06
1162893	Rock	1.90	<0.005	3.5	13.5	4.3	73	<0.1	3.9	14.8	1010	3.88	1.1	2.1	5.1	192	0.2	0.4	0.1	113	3.43
1162894	Rock	1.87	<0.005	2.0	9.0	5.8	50	<0.1	6.4	9.5	671	2.71	1.1	1.3	6.8	159	0.2	0.6	0.2	54	2.15
1162895	Rock	2.12	<0.005	2.1	6.6	12.2	51	<0.1	5.4	10.4	703	2.78	1.2	0.8	5.8	143	0.2	0.6	<0.1	60	2.21
1162896	Rock	1.91	0.008	2.1	6.1	6.3	52	<0.1	5.0	11.7	670	2.91	2.3	4.6	5.1	107	0.2	0.3	0.2	70	2.56
1162897	Rock	1.86	0.060	2.5	7.9	8.1	54	0.3	4.4	10.9	858	3.14	5.9	55.8	4.2	165	0.1	0.5	0.2	61	3.64
1162898	Rock	2.02	<0.005	2.8	5.2	7.1	51	<0.1	5.1	11.6	874	3.87	87.4	2.1	3.4	157	0.1	0.7	0.2	55	2.50
1162899	Rock	1.86	<0.005	1.7	10.1	2.9	67	<0.1	4.8	14.3	1011	5.00	1.4	0.9	5.0	146	<0.1	0.8	0.1	85	1.74
1162900	Rock Pulp	0.12	2.244	65.1	2242.2	1326.1	3714	26.5	188.9	20.8	632	5.53	1253.1	984.3	2.6	83	21.2	14.8	10.0	57	1.49
1162901	Rock	1.85	<0.005	3.7	6.9	15.4	53	<0.1	5.8	7.9	696	2.72	1.2	1.7	6.2	133	0.1	0.5	0.2	63	1.81
1162902	Rock	2.10	<0.005	2.2	7.0	2.6	31	<0.1	8.5	7.7	510	2.43	1.0	0.7	10.9	121	<0.1	0.3	<0.1	47	1.41
1162903	Rock	1.72	<0.005	2.1	8.3	2.3	36	<0.1	7.5	8.9	665	2.65	0.9	1.2	9.0	157	<0.1	0.2	<0.1	59	2.04
1162904	Rock	2.21	<0.005	1.8	6.6	2.3	45	<0.1	7.4	9.7	689	2.98	1.2	<0.5	6.8	126	<0.1	0.3	0.1	53	1.74
1162905	Rock	1.87	<0.005	1.8	5.2	2.1	40	<0.1	7.3	9.4	742	3.32	1.2	0.7	7.6	66	<0.1	0.2	0.2	48	1.59
1162906	Rock	2.01	<0.005	2.1	4.5	2.5	44	<0.1	7.0	11.3	812	3.97	1.0	<0.5	6.9	97	<0.1	0.2	0.3	51	2.56
1162907	Rock	1.93	<0.005	2.6	6.5	1.5	58	<0.1	7.0	14.8	883	4.64	1.2	1.7	8.0	62	<0.1	0.2	0.2	74	1.28
1162908	Rock	1.94	<0.005	2.3	9.4	1.7	52	<0.1	6.2	11.1	976	4.14	0.9	0.8	8.4	81	<0.1	0.2	0.2	69	1.81
1162909	Rock	1.67	<0.005	1.7	4.2	1.5	51	<0.1	5.6	12.5	876	4.07	0.8	<0.5	6.7	102	<0.1	0.1	0.2	78	1.39
1162910	Rock Pulp	0.12	0.801	4.1	31.7	5.2	49	0.3	24.0	9.3	399	2.56	5.9	714.7	0.9	43	0.2	0.8	0.1	61	0.88
1162911	Rock	2.20	<0.005	1.4	4.5	1.3	40	<0.1	6.3	10.3	763	3.19	0.9	1.2	4.5	71	<0.1	<0.1	0.1	65	1.18
1162912	Rock	1.97	<0.005	1.7	6.7	1.7	52	<0.1	5.3	12.1	838	3.74	2.0	1.0	4.7	74	<0.1	<0.1	<0.1	96	1.34
1162913	Rock	1.86	<0.005	2.1	7.0	2.1	60	<0.1	6.3	11.6	786	3.17	1.1	0.8	5.4	106	<0.1	0.1	<0.1	92	1.31
1162914	Rock	1.66	<0.005	2.5	11.6	2.7	60	<0.1	7.0	13.8	758	3.42	1.3	0.8	4.4	92	<0.1	<0.1	0.1	89	1.31
1162915	Rock	1.76	<0.005	2.6	10.8	4.6	61	<0.1	5.1	10.7	655	3.32	1.0	1.6	3.5	130	<0.1	<0.1	<0.1	84	1.27



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1162886	Rock	0.085	7	69	1.87	196	0.063	<20	1.97	0.038	0.81	0.1	0.03	17.5	0.2	<0.05	9	<0.5	<0.2
1162887	Rock	0.073	7	72	2.12	230	0.066	<20	2.14	0.044	0.58	0.1	0.05	18.8	0.1	0.09	9	<0.5	<0.2
1162888	Rock	0.059	10	60	1.60	471	0.092	<20	1.51	0.041	1.02	0.2	0.03	19.8	0.3	<0.05	7	<0.5	<0.2
1162889	Rock	0.048	6	51	2.08	398	0.048	<20	1.55	0.017	0.96	0.1	0.06	18.8	0.3	<0.05	6	<0.5	<0.2
1162890	Rock	0.048	5	48	2.09	340	0.043	<20	1.44	0.016	0.92	0.1	0.06	16.9	0.3	<0.05	6	<0.5	<0.2
1162891	Rock	0.127	10	21	1.47	810	0.066	<20	1.32	0.040	0.87	0.1	0.06	18.7	0.2	0.07	6	<0.5	<0.2
1162892	Rock	0.076	14	34	1.33	613	0.096	<20	1.41	0.051	1.11	0.2	0.08	16.2	0.3	<0.05	6	<0.5	0.3
1162893	Rock	0.053	12	12	1.47	820	0.100	<20	1.52	0.044	1.12	0.2	0.02	16.7	0.3	0.09	7	<0.5	<0.2
1162894	Rock	0.053	13	23	0.98	923	0.050	<20	1.01	0.043	0.66	0.2	0.03	11.5	0.2	<0.05	4	<0.5	<0.2
1162895	Rock	0.052	13	14	1.04	1069	0.025	<20	0.84	0.034	0.48	0.3	0.03	14.2	0.1	0.07	4	<0.5	<0.2
1162896	Rock	0.047	8	15	1.25	687	0.035	<20	1.08	0.026	0.63	0.2	0.04	15.5	0.2	0.14	5	<0.5	<0.2
1162897	Rock	0.018	6	12	1.09	804	0.006	<20	0.62	0.007	0.26	0.4	0.14	11.2	<0.1	0.08	2	<0.5	0.2
1162898	Rock	0.020	5	15	0.90	2202	0.013	<20	0.71	0.008	0.28	0.4	0.50	10.5	<0.1	0.12	2	<0.5	<0.2
1162899	Rock	0.050	13	17	1.12	1580	0.130	<20	1.43	0.049	0.94	1.1	0.04	13.1	0.2	0.25	6	<0.5	<0.2
1162900	Rock Pulp	0.063	12	44	0.87	158	0.089	<20	1.54	0.086	0.20	8.8	0.82	4.5	1.2	1.52	6	4.5	0.6
1162901	Rock	0.054	15	25	0.93	1605	0.099	<20	1.15	0.070	0.65	1.1	0.03	9.0	0.1	0.05	5	<0.5	<0.2
1162902	Rock	0.073	33	33	0.81	1376	0.098	<20	1.03	0.065	0.60	1.5	0.03	7.1	0.1	0.06	6	<0.5	<0.2
1162903	Rock	0.059	21	26	1.04	1961	0.119	<20	1.25	0.072	0.72	1.5	0.02	7.5	0.2	0.11	7	<0.5	<0.2
1162904	Rock	0.047	15	24	0.97	1111	0.104	<20	1.42	0.045	0.73	1.1	0.01	6.2	0.2	0.06	7	<0.5	<0.2
1162905	Rock	0.044	17	23	0.93	846	0.110	<20	1.53	0.043	0.84	0.7	0.03	6.7	0.2	<0.05	7	<0.5	<0.2
1162906	Rock	0.046	20	23	0.95	641	0.079	<20	1.56	0.029	0.58	0.8	0.06	8.0	0.1	0.14	7	<0.5	<0.2
1162907	Rock	0.049	17	27	1.28	1459	0.187	<20	2.00	0.052	1.21	1.2	0.02	9.7	0.2	0.16	9	<0.5	<0.2
1162908	Rock	0.049	23	25	1.03	1202	0.154	<20	1.83	0.039	0.96	0.6	0.02	9.3	0.2	0.06	8	<0.5	<0.2
1162909	Rock	0.049	18	24	1.30	1161	0.171	<20	1.98	0.052	1.01	0.4	0.01	10.5	0.2	0.14	9	<0.5	<0.2
1162910	Rock Pulp	0.062	5	33	0.75	100	0.137	<20	1.59	0.090	0.14	10.7	0.05	5.5	<0.1	<0.05	5	<0.5	<0.2
1162911	Rock	0.056	13	27	1.20	663	0.197	<20	1.63	0.061	1.00	1.8	<0.01	6.6	0.2	0.15	6	<0.5	<0.2
1162912	Rock	0.042	13	24	1.41	551	0.185	<20	1.64	0.093	1.00	1.3	0.03	8.6	0.2	0.28	7	<0.5	<0.2
1162913	Rock	0.050	11	24	1.43	610	0.216	<20	1.60	0.085	1.07	1.7	0.01	8.4	0.2	0.21	8	<0.5	<0.2
1162914	Rock	0.047	11	21	1.20	624	0.223	<20	1.49	0.098	1.09	2.2	0.01	7.8	0.3	0.44	7	<0.5	<0.2
1162915	Rock	0.034	10	19	0.92	679	0.162	<20	1.13	0.066	0.79	2.7	<0.01	9.4	0.2	0.43	6	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162916	Rock	2.00	<0.005	3.2	6.6	2.9	57	<0.1	5.6	15.5	754	4.97	1.6	0.8	4.4	66	<0.1	<0.1	<0.1	96	0.86
1162917	Rock	1.92	<0.005	3.0	12.2	1.2	69	<0.1	7.1	15.5	893	5.41	0.9	1.1	6.3	81	<0.1	<0.1	<0.1	93	0.88
1162918	Rock	1.89	<0.005	3.7	7.9	0.8	61	<0.1	7.1	14.5	818	4.34	1.6	2.4	5.1	40	<0.1	<0.1	<0.1	85	0.61
1162919	Rock	1.86	<0.005	1.9	12.5	2.0	50	<0.1	7.5	11.1	652	3.12	0.6	0.6	5.5	71	<0.1	<0.1	<0.1	68	0.72
1162920	Rock	0.77	<0.005	0.3	0.6	1.0	13	<0.1	1.1	0.7	226	0.46	<0.5	0.6	<0.1	42	<0.1	<0.1	<0.1	<2	20.08
1162921	Rock	2.57	<0.005	2.3	7.6	1.5	38	<0.1	6.1	7.4	552	2.76	0.6	0.6	7.3	91	<0.1	<0.1	<0.1	64	0.90
1162922	Rock	1.78	<0.005	2.4	7.4	1.1	37	<0.1	7.1	7.9	529	2.82	0.9	1.0	6.0	65	<0.1	<0.1	0.1	57	0.79
1162923	Rock	1.95	<0.005	2.3	6.0	1.6	32	<0.1	7.0	6.3	491	2.15	0.5	0.8	4.4	99	<0.1	<0.1	<0.1	39	0.78
1162924	Rock	1.93	<0.005	2.5	18.1	2.4	48	<0.1	7.8	7.9	463	2.28	0.6	1.7	5.2	63	<0.1	<0.1	<0.1	41	0.85
1162925	Rock	1.74	<0.005	2.2	11.1	2.6	64	<0.1	6.2	10.8	625	2.87	0.7	<0.5	4.5	73	<0.1	<0.1	<0.1	66	1.01
1162926	Rock	2.12	<0.005	2.5	10.6	3.0	87	<0.1	6.6	11.3	672	3.11	1.1	<0.5	5.0	64	0.2	<0.1	0.1	69	0.77
1162927	Rock	2.02	<0.005	2.3	7.7	2.9	85	<0.1	7.4	9.0	509	2.64	0.8	<0.5	7.0	31	0.2	<0.1	0.1	59	0.55
1162928	Rock	1.93	<0.005	2.8	6.9	5.0	65	<0.1	13.4	9.8	445	2.54	0.8	0.7	5.8	70	0.1	<0.1	<0.1	53	0.75
1162929	Rock	1.90	<0.005	2.5	14.8	7.4	86	<0.1	11.6	10.3	558	2.88	0.9	3.8	5.7	77	0.1	0.1	<0.1	68	1.05
1162930	Rock	1.39	<0.005	2.4	14.5	7.1	82	<0.1	10.3	9.9	566	2.81	0.8	1.7	5.6	78	0.1	<0.1	<0.1	67	1.03
1162931	Rock	1.79	0.010	2.8	11.3	6.0	124	<0.1	9.0	15.6	878	3.72	1.1	7.4	4.3	96	0.2	<0.1	0.1	85	1.52
1162932	Rock	1.60	0.010	2.4	19.5	4.8	128	0.1	9.9	17.5	901	4.30	1.3	8.5	6.1	74	0.4	<0.1	0.1	77	1.17
1162933	Rock	1.90	<0.005	2.4	10.9	4.3	79	<0.1	9.5	12.5	651	3.19	0.8	<0.5	3.7	71	0.2	<0.1	<0.1	78	1.06
1162934	Rock	1.88	<0.005	2.7	8.7	5.2	80	<0.1	11.6	10.8	616	2.75	0.7	<0.5	5.8	98	0.2	0.1	0.1	62	0.99
1162935	Rock	2.21	0.008	1.3	24.9	5.5	67	<0.1	11.3	9.4	493	2.38	3.6	2.9	5.5	95	0.1	0.3	<0.1	54	1.08
1162936	Rock	2.05	<0.005	2.2	12.7	5.6	65	<0.1	7.2	7.9	449	2.35	1.3	<0.5	5.2	52	0.2	0.2	<0.1	57	0.95
1162937	Rock	1.27	0.202	4.3	22.2	11.3	110	1.0	8.8	13.5	717	3.48	1.3	119.5	6.2	100	0.3	0.2	0.1	80	1.45
1162938	Rock	2.09	0.118	3.7	15.0	10.8	82	0.7	7.0	11.2	899	3.05	0.7	92.5	5.8	499	0.3	0.1	0.1	71	2.58
1162939	Rock	1.75	0.041	4.0	10.4	7.1	85	0.2	7.6	11.6	748	3.29	0.7	29.9	5.5	488	0.2	0.1	0.1	76	1.53
1162940	Rock Pulp	0.12	2.385	68.4	2195.3	1340.7	3645	26.6	188.7	20.9	634	5.39	1230.7	855.9	2.8	77	22.4	15.2	10.3	56	1.51
1162941	Rock	2.05	0.036	3.7	9.4	7.1	71	0.2	5.4	10.2	668	3.04	1.6	20.0	9.5	200	0.2	0.2	0.2	64	1.33
1162942	Rock	1.93	0.020	5.1	10.6	8.0	75	0.2	7.7	10.9	865	3.40	6.9	18.4	8.5	239	0.2	0.2	0.2	75	1.37
1162943	Rock	1.63	0.026	3.6	10.6	5.9	70	0.2	6.4	11.5	721	3.39	1.8	23.6	6.2	138	0.1	0.1	<0.1	85	1.20
1162944	Rock	1.60	0.012	2.7	8.5	5.7	77	0.1	4.4	15.6	1051	4.17	1.9	12.0	6.4	173	0.2	0.2	0.2	97	2.36
1162945	Rock	2.19	0.011	3.4	13.4	4.0	68	0.1	7.1	12.6	893	3.85	1.3	11.0	7.4	132	0.1	<0.1	0.1	84	1.20



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1162916	Rock	0.050	11	23	1.30	1095	0.256	<20	1.95	0.093	1.45	2.1	0.01	8.5	0.3	0.43	8	<0.5	<0.2
1162917	Rock	0.052	17	30	1.53	852	0.273	<20	2.11	0.081	1.73	1.7	<0.01	8.4	0.4	0.45	9	<0.5	<0.2
1162918	Rock	0.060	11	30	1.48	1378	0.269	<20	2.09	0.105	1.52	2.7	<0.01	6.2	0.3	0.42	9	<0.5	<0.2
1162919	Rock	0.062	16	27	1.00	930	0.231	<20	1.49	0.100	1.04	2.3	<0.01	5.9	0.3	0.19	7	<0.5	<0.2
1162920	Rock	0.012	<1	<1	11.66	34	0.003	<20	0.04	<0.001	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2
1162921	Rock	0.056	18	28	0.92	1254	0.189	<20	1.35	0.126	0.79	2.4	<0.01	7.7	0.2	0.08	6	<0.5	<0.2
1162922	Rock	0.052	16	27	0.92	831	0.148	<20	1.36	0.107	0.76	2.5	0.01	6.0	0.1	0.15	7	<0.5	<0.2
1162923	Rock	0.038	10	28	0.80	486	0.169	<20	1.22	0.057	0.81	1.8	<0.01	3.6	0.2	0.11	6	<0.5	<0.2
1162924	Rock	0.056	14	25	0.80	363	0.185	<20	1.30	0.064	0.87	2.0	0.01	3.3	0.2	0.13	6	<0.5	<0.2
1162925	Rock	0.053	11	23	1.28	477	0.203	<20	1.67	0.067	1.16	1.6	<0.01	4.8	0.2	0.13	7	<0.5	<0.2
1162926	Rock	0.058	9	24	1.31	738	0.239	<20	1.78	0.104	1.20	1.9	<0.01	6.2	0.2	0.26	8	<0.5	<0.2
1162927	Rock	0.053	10	29	1.03	792	0.205	<20	1.45	0.107	0.92	2.7	<0.01	6.4	0.2	0.13	7	<0.5	<0.2
1162928	Rock	0.063	12	39	1.22	531	0.239	<20	1.70	0.084	1.19	0.9	<0.01	4.9	0.2	<0.05	8	<0.5	<0.2
1162929	Rock	0.072	14	39	1.36	566	0.240	<20	1.79	0.076	1.17	0.9	0.01	5.6	0.2	<0.05	8	<0.5	<0.2
1162930	Rock	0.070	14	36	1.32	542	0.242	<20	1.77	0.080	1.14	0.8	<0.01	5.2	0.2	<0.05	8	<0.5	<0.2
1162931	Rock	0.071	10	30	1.76	842	0.274	<20	2.30	0.066	1.59	1.0	<0.01	6.3	0.3	0.17	9	<0.5	<0.2
1162932	Rock	0.064	14	31	1.66	869	0.239	<20	2.29	0.063	1.56	1.1	0.02	5.6	0.3	0.40	9	<0.5	<0.2
1162933	Rock	0.068	9	29	1.43	891	0.211	<20	1.80	0.064	1.15	1.4	<0.01	5.1	0.2	0.11	8	<0.5	<0.2
1162934	Rock	0.064	13	36	1.26	437	0.202	<20	1.68	0.077	1.11	1.9	<0.01	5.3	0.3	0.13	9	<0.5	<0.2
1162935	Rock	0.051	12	28	0.87	316	0.117	<20	1.15	0.047	0.70	0.3	0.06	6.1	0.2	<0.05	6	<0.5	<0.2
1162936	Rock	0.054	12	23	0.93	347	0.156	<20	1.27	0.070	0.78	0.3	0.01	5.7	0.2	<0.05	6	<0.5	<0.2
1162937	Rock	0.062	16	27	1.41	523	0.165	<20	1.75	0.056	1.04	1.4	0.10	7.4	0.3	0.23	9	<0.5	0.6
1162938	Rock	0.058	18	26	1.18	693	0.150	<20	1.55	0.073	0.85	1.9	0.05	7.6	0.2	0.17	7	<0.5	0.5
1162939	Rock	0.056	14	26	1.42	786	0.179	<20	1.82	0.065	1.12	1.7	0.03	6.3	0.2	0.17	8	<0.5	<0.2
1162940	Rock Pulp	0.065	12	50	0.90	177	0.098	<20	1.53	0.082	0.20	8.7	0.76	4.4	1.3	1.50	6	3.8	0.5
1162941	Rock	0.044	25	23	1.29	647	0.121	<20	1.61	0.062	0.88	1.3	0.02	8.0	0.2	0.21	8	<0.5	<0.2
1162942	Rock	0.059	21	27	1.65	629	0.181	<20	2.07	0.046	1.32	1.1	0.05	7.9	0.3	0.40	9	<0.5	<0.2
1162943	Rock	0.060	16	26	1.60	818	0.211	<20	2.09	0.078	1.42	1.4	0.03	6.9	0.3	0.26	9	<0.5	<0.2
1162944	Rock	0.058	18	17	1.92	885	0.172	<20	2.47	0.044	1.22	0.8	0.03	9.7	0.3	0.31	9	<0.5	<0.2
1162945	Rock	0.053	17	28	1.61	872	0.212	<20	2.16	0.067	1.44	1.3	0.01	8.1	0.3	0.39	9	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1162946	Rock	2.49	0.016	3.5	10.9	3.4	53	<0.1	7.7	9.9	771	2.95	1.3	9.2	8.7	173	<0.1	0.1	0.1	55	1.33
1162947	Rock	2.10	0.013	4.2	13.1	3.0	62	0.1	8.0	11.5	739	3.05	1.2	12.1	6.8	138	<0.1	<0.1	<0.1	63	1.21
1162948	Rock	1.84	0.011	4.3	8.1	3.7	61	<0.1	8.0	9.6	714	2.89	1.1	6.7	6.2	118	<0.1	<0.1	<0.1	68	1.40
1162949	Rock	1.79	0.009	5.8	9.4	4.5	63	<0.1	8.6	10.8	742	3.10	0.8	20.1	5.9	115	<0.1	<0.1	<0.1	64	1.50
1162950	Rock	0.77	<0.005	<0.1	1.1	1.3	14	<0.1	2.0	0.7	199	0.39	<0.5	<0.5	<0.1	48	<0.1	<0.1	<0.1	<2	19.81
1162951	Rock	1.43	0.107	11.2	14.2	5.3	64	0.1	8.8	10.9	673	2.86	1.1	32.0	7.0	256	0.1	0.1	<0.1	58	1.70
1162952	Rock	1.22	0.067	7.3	11.1	4.6	54	0.2	8.8	9.2	557	2.66	1.0	33.4	6.8	130	0.1	0.1	<0.1	52	1.26
1162953	Rock	1.49	0.033	6.6	11.8	5.1	54	0.8	9.2	9.6	556	2.70	1.2	55.4	7.0	207	0.1	0.2	<0.1	53	1.27
1184501	Rock	1.73	0.009	0.6	54.0	6.4	107	<0.1	6.9	15.5	859	3.90	3.3	8.9	1.2	33	0.2	0.5	<0.1	95	0.62
1184502	Rock	2.47	0.005	0.9	79.7	1.3	204	<0.1	2.6	11.0	1017	3.67	2.3	5.6	1.1	35	0.3	0.3	<0.1	75	0.70
1184503	Rock	2.86	<0.005	0.7	42.5	2.2	131	<0.1	3.2	12.2	950	3.88	5.4	2.0	0.6	41	0.2	0.2	<0.1	82	0.63
1184504	Rock	1.15	0.005	1.5	22.9	2.8	77	<0.1	5.7	11.8	1113	3.81	6.5	5.8	1.1	51	0.2	0.9	<0.1	87	0.39
1184505	Rock	2.81	0.022	1.3	46.6	2.0	194	<0.1	2.7	15.4	1136	4.10	49.6	17.7	0.7	41	0.3	0.2	<0.1	88	0.44
1184506	Rock	2.49	<0.005	0.9	27.6	2.4	104	<0.1	3.8	12.9	1000	3.89	41.5	2.9	0.8	65	0.2	0.2	<0.1	88	0.45
1184507	Rock	1.23	<0.005	0.9	19.2	1.6	94	<0.1	2.7	15.1	1060	4.36	13.3	2.3	1.1	41	0.3	1.4	<0.1	124	0.44
1184508	Rock	2.24	<0.005	0.8	66.3	0.8	74	<0.1	2.2	12.8	899	3.59	4.0	1.5	0.7	50	<0.1	0.8	<0.1	74	0.62
1184509	Rock	1.99	<0.005	0.8	49.6	1.9	62	<0.1	5.3	10.9	701	3.42	3.6	2.3	0.9	78	<0.1	0.2	<0.1	77	0.65
1184510	Rock Pulp	0.12	0.905	4.8	37.0	5.6	55	0.2	26.5	10.4	415	2.53	6.7	428.3	1.0	40	0.2	0.9	0.1	61	0.85
1184511	Rock	1.30	<0.005	0.8	44.2	2.0	57	<0.1	6.6	15.5	610	3.61	3.4	1.4	1.2	56	0.1	0.2	<0.1	101	0.62
1184512	Rock	1.48	<0.005	0.6	37.5	1.8	68	<0.1	9.8	16.9	605	3.57	3.3	1.8	1.1	55	0.1	0.2	<0.1	108	0.67
1184513	Rock	1.77	<0.005	0.6	44.7	1.4	63	<0.1	8.1	17.0	666	3.77	3.2	1.2	1.0	57	<0.1	0.2	<0.1	114	0.64
1184514	Rock	2.52	<0.005	0.7	30.1	2.7	79	<0.1	11.8	18.8	706	3.63	3.0	1.8	0.8	67	<0.1	0.1	<0.1	104	0.75
1184515	Rock	2.02	<0.005	0.7	20.9	2.8	57	<0.1	7.9	13.6	549	2.65	1.9	1.0	0.8	50	<0.1	<0.1	<0.1	74	0.78
1184516	Rock	1.65	<0.005	0.8	46.9	4.0	66	<0.1	8.3	14.5	608	3.12	2.0	1.7	0.7	66	<0.1	<0.1	<0.1	90	0.76
1184517	Rock	2.75	<0.005	0.8	72.5	1.3	72	<0.1	8.1	16.0	649	3.49	2.7	1.5	0.8	62	0.1	<0.1	<0.1	96	0.91
1184518	Rock	2.41	<0.005	0.8	52.0	3.1	132	<0.1	12.2	21.4	958	4.66	3.3	0.9	1.1	91	<0.1	<0.1	<0.1	145	1.25
1184519	Rock	2.26	<0.005	0.7	121.4	2.0	76	<0.1	15.3	25.1	783	4.77	3.7	3.6	0.5	84	<0.1	0.1	<0.1	189	1.84
1184520	Rock	0.75	<0.005	0.1	1.6	1.2	12	<0.1	1.1	1.2	226	0.47	<0.5	<0.5	<0.1	48	<0.1	<0.1	<0.1	7	19.15
1184521	Rock	2.46	<0.005	0.9	89.2	1.3	67	<0.1	11.5	24.2	793	4.49	3.8	2.5	0.8	97	<0.1	0.1	<0.1	156	2.32
1184522	Rock	2.24	<0.005	1.2	119.9	1.1	67	<0.1	10.0	21.7	617	4.17	2.5	1.2	1.2	107	0.1	<0.1	<0.1	139	2.19



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1162946	Rock	0.057	21	31	1.29	600	0.186	<20	1.76	0.059	1.22	1.7	0.02	6.5	0.3	0.27	7	<0.5	<0.2
1162947	Rock	0.053	16	31	1.49	589	0.192	<20	1.92	0.055	1.38	2.0	0.02	5.4	0.4	0.30	8	<0.5	<0.2
1162948	Rock	0.052	15	39	1.29	578	0.176	<20	1.63	0.073	0.97	1.2	0.01	7.9	0.2	0.13	7	<0.5	<0.2
1162949	Rock	0.056	13	55	1.37	568	0.199	<20	1.68	0.061	1.05	1.6	0.02	7.2	0.2	0.24	8	<0.5	<0.2
1162950	Rock	0.016	<1	<1	11.25	20	0.001	<20	0.03	0.002	0.02	<0.1	<0.01	0.6	<0.1	<0.05	<1	<0.5	<0.2
1162951	Rock	0.051	17	44	1.10	606	0.143	<20	1.46	0.066	0.86	1.1	0.02	7.2	0.2	0.23	7	<0.5	<0.2
1162952	Rock	0.049	17	51	1.05	549	0.145	<20	1.38	0.050	0.88	0.8	0.05	6.1	0.2	0.18	7	<0.5	<0.2
1162953	Rock	0.050	17	48	1.06	521	0.145	<20	1.41	0.061	0.88	0.7	0.06	6.2	0.2	0.17	6	<0.5	0.4
1184501	Rock	0.088	6	23	0.98	356	0.139	<20	1.35	0.082	0.49	0.4	0.07	14.8	0.1	<0.05	7	<0.5	<0.2
1184502	Rock	0.098	6	8	0.80	305	0.125	<20	1.15	0.116	0.45	0.3	0.10	11.6	0.1	<0.05	6	<0.5	<0.2
1184503	Rock	0.084	3	8	1.01	825	0.199	<20	1.50	0.083	0.78	0.5	0.12	9.9	0.2	<0.05	6	<0.5	<0.2
1184504	Rock	0.099	7	8	0.34	446	0.064	<20	0.62	0.078	0.24	0.6	0.08	14.7	<0.1	<0.05	4	<0.5	<0.2
1184505	Rock	0.086	4	8	0.92	885	0.164	<20	1.54	0.062	0.87	0.5	0.18	11.6	0.2	<0.05	6	<0.5	<0.2
1184506	Rock	0.097	5	8	0.94	778	0.134	<20	1.34	0.067	0.64	0.4	0.16	13.0	0.2	<0.05	7	<0.5	<0.2
1184507	Rock	0.114	8	8	0.47	299	0.056	<20	0.93	0.064	0.29	0.5	0.11	16.4	<0.1	<0.05	5	<0.5	<0.2
1184508	Rock	0.099	5	7	0.68	371	0.098	<20	1.11	0.090	0.38	0.3	0.04	11.2	<0.1	<0.05	6	<0.5	<0.2
1184509	Rock	0.088	5	14	0.69	1363	0.133	<20	0.92	0.137	0.25	0.3	0.04	10.6	<0.1	<0.05	5	<0.5	<0.2
1184510	Rock Pulp	0.067	5	38	0.74	107	0.130	<20	1.56	0.090	0.14	10.4	0.05	5.4	<0.1	<0.05	5	<0.5	<0.2
1184511	Rock	0.082	7	23	1.20	612	0.119	<20	1.36	0.110	0.49	0.1	0.03	11.6	<0.1	<0.05	6	<0.5	<0.2
1184512	Rock	0.072	6	44	1.55	538	0.182	<20	1.64	0.105	0.64	0.1	0.05	11.2	0.1	<0.05	7	<0.5	<0.2
1184513	Rock	0.071	5	27	1.57	264	0.150	<20	1.66	0.099	0.62	0.1	0.02	11.2	0.1	<0.05	7	<0.5	<0.2
1184514	Rock	0.083	4	66	2.04	239	0.208	<20	1.97	0.105	0.90	0.3	0.03	10.2	0.2	<0.05	8	<0.5	<0.2
1184515	Rock	0.072	4	53	1.28	184	0.198	<20	1.26	0.121	0.56	0.4	0.02	8.0	0.1	<0.05	5	<0.5	<0.2
1184516	Rock	0.081	3	22	1.45	207	0.195	<20	1.57	0.116	0.73	0.3	0.02	8.3	0.2	<0.05	6	<0.5	<0.2
1184517	Rock	0.078	4	20	1.69	168	0.152	<20	1.75	0.116	0.69	0.2	0.02	10.6	0.2	<0.05	7	<0.5	<0.2
1184518	Rock	0.089	5	25	2.39	419	0.198	<20	2.60	0.066	1.43	0.3	0.03	16.4	0.4	<0.05	10	<0.5	<0.2
1184519	Rock	0.057	3	28	2.29	268	0.173	<20	2.51	0.088	1.44	1.3	0.04	15.3	0.4	<0.05	9	<0.5	<0.2
1184520	Rock	0.019	<1	<1	11.94	38	0.003	<20	0.05	<0.001	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2
1184521	Rock	0.084	5	33	1.76	183	0.133	<20	1.92	0.102	0.77	0.4	0.02	17.7	0.2	<0.05	7	<0.5	<0.2
1184522	Rock	0.087	6	11	1.43	252	0.135	<20	1.76	0.099	0.81	0.3	<0.01	13.7	0.1	<0.05	8	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 6 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1184523	Rock	2.01	<0.005	0.9	103.6	1.1	71	<0.1	16.1	23.7	676	4.46	2.0	1.0	1.7	92	<0.1	0.1	<0.1	133	1.82
1184524	Rock	2.12	<0.005	1.1	58.6	2.0	60	<0.1	22.8	18.8	754	3.80	8.7	0.7	1.5	239	<0.1	3.1	<0.1	86	2.90
1184525	Rock	2.00	<0.005	2.2	36.2	2.5	63	<0.1	9.4	14.0	832	3.68	25.4	2.4	0.8	208	<0.1	5.1	<0.1	66	2.71
1184526	Rock	2.48	<0.005	2.8	21.4	4.9	76	<0.1	12.1	22.2	1046	4.55	197.8	1.9	0.9	165	0.1	3.0	<0.1	71	2.35
1184527	Rock	1.67	<0.005	1.7	28.8	2.6	74	<0.1	10.3	23.0	933	4.50	67.8	<0.5	1.2	188	<0.1	4.1	<0.1	106	3.51
1184528	Rock	2.37	<0.005	4.4	16.3	4.7	84	<0.1	15.4	25.3	1228	5.05	128.3	1.1	1.3	334	0.2	3.2	<0.1	108	4.26
1184529	Rock	2.61	<0.005	4.2	63.3	3.8	76	<0.1	12.9	20.9	1127	4.53	84.5	2.1	1.1	234	0.2	3.1	<0.1	91	3.54
1184530	Rock	0.89	<0.005	4.7	59.2	4.0	76	<0.1	12.7	21.2	1151	4.48	75.1	1.2	1.0	234	0.2	2.9	<0.1	91	3.53
1184531	Rock	2.37	<0.005	4.3	66.3	6.0	88	0.1	9.5	22.2	1327	4.60	53.1	2.9	1.5	268	0.3	8.9	<0.1	108	4.09
1184532	Rock	2.40	0.008	4.1	62.5	7.0	82	0.1	13.0	18.3	1121	4.11	59.7	6.8	5.1	235	0.2	5.4	0.1	71	4.22
1167670	Rock Pulp	0.13	0.817	4.2	34.1	5.5	54	0.3	24.2	10.5	402	2.49	7.3	646.7	0.9	38	0.2	0.9	0.1	59	0.80
1167671	Rock	1.62	0.046	4.6	7.1	8.1	44	<0.1	6.5	7.6	549	2.10	4.5	76.8	9.5	130	<0.1	0.7	<0.1	24	2.12
1167672	Rock	1.59	0.040	2.1	6.4	5.9	21	0.1	3.4	3.5	459	1.41	2.5	22.9	8.1	95	<0.1	0.5	<0.1	15	1.42
1167673	Rock	1.97	0.018	2.9	7.4	9.2	36	<0.1	4.9	6.6	708	2.10	1.7	12.7	7.1	130	0.2	0.5	<0.1	29	2.17
1167674	Rock	2.70	0.900	41.5	42.1	1239.3	29	5.8	6.3	7.2	925	2.44	2.9	791.7	3.3	152	0.5	4.5	4.9	14	1.89
1167675	Rock	2.44	1.250	44.7	73.5	1761.8	15	7.1	2.8	2.5	258	1.19	4.8	1201.0	9.4	103	0.2	14.6	6.9	6	0.45
1167676	Rock	1.43	0.187	4.5	18.1	143.2	12	0.7	1.8	1.4	301	1.01	2.2	172.3	12.2	76	<0.1	1.8	0.5	5	0.91
1167677	Rock	2.27	0.458	36.7	14.0	49.7	26	1.4	1.6	4.5	428	2.22	2.8	382.9	6.7	81	<0.1	0.9	0.4	11	0.97
1167678	Rock	1.38	0.270	12.3	14.5	91.8	34	0.9	2.2	4.9	529	2.56	4.2	337.5	8.0	112	0.1	1.1	0.5	12	1.26
1167679	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000286.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1184523	Rock	0.089	8	25	1.64	554	0.157	<20	2.05	0.116	1.21	<0.1	0.02	14.9	0.2	<0.05	8	<0.5	<0.2
1184524	Rock	0.071	6	27	1.15	2531	0.047	<20	1.06	0.049	0.50	0.2	0.83	16.4	0.2	0.07	4	<0.5	<0.2
1184525	Rock	0.026	3	14	0.69	1007	0.006	<20	0.68	0.009	0.14	0.5	0.87	14.3	0.3	<0.05	2	<0.5	<0.2
1184526	Rock	0.042	3	29	0.36	875	0.004	<20	0.60	0.018	0.20	1.3	2.47	19.9	1.2	<0.05	2	<0.5	<0.2
1184527	Rock	0.085	5	25	0.88	772	0.008	<20	0.59	0.036	0.26	0.6	1.24	21.3	0.3	<0.05	2	<0.5	<0.2
1184528	Rock	0.064	7	62	1.07	3704	0.006	<20	0.58	0.029	0.28	1.0	2.93	27.0	1.1	0.09	2	<0.5	<0.2
1184529	Rock	0.067	5	34	0.88	2014	0.004	<20	0.71	0.020	0.37	0.8	3.99	22.0	0.9	0.05	2	<0.5	<0.2
1184530	Rock	0.059	5	32	0.85	2027	0.004	<20	0.72	0.021	0.36	0.7	3.43	21.1	0.9	0.05	2	<0.5	<0.2
1184531	Rock	0.032	3	17	0.86	2018	0.005	<20	0.49	0.020	0.21	1.0	3.40	20.8	0.5	0.05	2	<0.5	<0.2
1184532	Rock	0.033	11	22	0.69	1128	0.004	<20	0.66	0.017	0.37	0.7	1.60	17.0	0.5	<0.05	3	<0.5	<0.2
1167670	Rock Pulp	0.064	5	35	0.72	104	0.118	<20	1.51	0.085	0.13	10.3	0.07	4.8	<0.1	<0.05	5	<0.5	<0.2
1167671	Rock	0.051	16	12	0.70	1203	0.008	<20	0.44	0.030	0.28	0.6	0.12	7.4	<0.1	0.11	2	<0.5	<0.2
1167672	Rock	0.018	17	7	0.50	1254	0.005	<20	0.32	0.032	0.21	0.2	0.17	6.6	<0.1	0.09	1	<0.5	<0.2
1167673	Rock	0.041	14	12	0.83	1286	0.007	<20	0.31	0.043	0.19	0.7	0.12	9.6	<0.1	0.13	1	<0.5	<0.2
1167674	Rock	0.025	9	12	0.74	480	<0.001	<20	0.25	0.025	0.14	1.5	1.90	9.8	<0.1	0.48	<1	1.8	4.3
1167675	Rock	0.006	11	9	0.18	2246	<0.001	<20	0.20	0.027	0.12	2.8	2.81	3.8	<0.1	0.18	<1	2.8	5.6
1167676	Rock	0.004	11	8	0.33	1306	<0.001	<20	0.28	0.015	0.18	0.7	0.53	2.9	<0.1	0.18	<1	<0.5	0.6
1167677	Rock	0.044	9	6	0.33	807	0.004	<20	0.40	0.010	0.26	0.4	0.27	5.9	<0.1	0.29	1	<0.5	1.2
1167678	Rock	0.054	12	10	0.43	1443	0.005	<20	0.46	0.018	0.30	0.3	0.31	6.9	<0.1	0.26	2	0.5	0.7
1167679	Rock	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.



QUALITY CONTROL REPORT

WHI16000286.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1162874	Rock	1.99	0.008	1.2	80.2	4.2	49	<0.1	29.8	21.8	774	3.58	5.5	5.5	3.1	96	0.2	0.7	<0.1	78	3.29
REP 1162874	QC	0.008																			
1162886	Rock	2.07	<0.005	1.4	56.6	1.9	92	<0.1	29.1	24.1	1039	4.40	5.2	1.9	0.7	96	0.1	0.3	<0.1	113	3.35
REP 1162886	QC	1.4 54.3 1.8 88 <0.1 28.2 24.0 1034 4.43 5.1 3.0 0.7 90 0.1 0.4 <0.1 113 3.32																			
1162920	Rock	0.77	<0.005	0.3	0.6	1.0	13	<0.1	1.1	0.7	226	0.46	<0.5	0.6	<0.1	42	<0.1	<0.1	<0.1	<2	20.08
REP 1162920	QC	<0.005																			
1162921	Rock	2.57	<0.005	2.3	7.6	1.5	38	<0.1	6.1	7.4	552	2.76	0.6	0.6	7.3	91	<0.1	<0.1	<0.1	64	0.90
REP 1162921	QC	2.2 8.1 1.6 39 <0.1 6.6 7.7 550 2.85 0.8 1.5 7.3 90 <0.1 <0.1 <0.1 65 0.96																			
1162948	Rock	1.84	0.011	4.3	8.1	3.7	61	<0.1	8.0	9.6	714	2.89	1.1	6.7	6.2	118	<0.1	<0.1	<0.1	68	1.40
REP 1162948	QC	0.010																			
1184503	Rock	2.86	<0.005	0.7	42.5	2.2	131	<0.1	3.2	12.2	950	3.88	5.4	2.0	0.6	41	0.2	0.2	<0.1	82	0.63
REP 1184503	QC	0.7 42.7 2.2 131 <0.1 3.3 13.2 965 3.94 5.3 3.3 0.6 43 0.2 0.2 <0.1 82 0.64																			
1167675	Rock	2.44	1.250	44.7	73.5	1761.8	15	7.1	2.8	2.5	258	1.19	4.8	1201.0	9.4	103	0.2	14.6	6.9	6	0.45
REP 1167675	QC	44.5 73.6 1788.2 15 7.2 2.8 2.6 265 1.21 5.1 1173.3 9.5 103 0.2 13.9 6.8 6 0.46																			
1167678	Rock	1.38	0.270	12.3	14.5	91.8	34	0.9	2.2	4.9	529	2.56	4.2	337.5	8.0	112	0.1	1.1	0.5	12	1.26
REP 1167678	QC	0.257 11.5 13.0 87.7 32 0.9 2.2 4.4 499 2.38 3.8 267.7 7.7 112 0.1 1.1 0.5 12 1.19																			
Core Reject Duplicates																					
1162878	Rock	1.96	0.007	1.4	69.1	3.6	66	<0.1	42.2	25.1	1552	4.56	1.7	3.5	1.6	126	0.2	0.7	<0.1	106	6.47
DUP 1162878	QC	<0.005 1.3 63.9 3.4 62 <0.1 39.2 23.7 1509 4.39 1.6 3.3 1.6 115 0.2 0.6 <0.1 102 6.32																			
1162912	Rock	1.97	<0.005	1.7	6.7	1.7	52	<0.1	5.3	12.1	838	3.74	2.0	1.0	4.7	74	<0.1	<0.1	<0.1	96	1.34
DUP 1162912	QC	<0.005 1.8 7.7 1.8 59 <0.1 5.4 13.1 887 3.96 2.1 1.1 5.0 81 <0.1 <0.1 <0.1 102 1.43																			
1162946	Rock	2.49	0.016	3.5	10.9	3.4	53	<0.1	7.7	9.9	771	2.95	1.3	9.2	8.7	173	<0.1	0.1	0.1	55	1.33
DUP 1162946	QC	0.019 3.5 10.7 3.3 52 <0.1 7.5 10.6 778 2.96 1.3 6.9 8.8 171 <0.1 <0.1 0.1 55 1.35																			
1184527	Rock	1.67	<0.005	1.7	28.8	2.6	74	<0.1	10.3	23.0	933	4.50	67.8	<0.5	1.2	188	<0.1	4.1	<0.1	106	3.51
DUP 1184527	QC	<0.005 1.9 29.1 2.7 72 <0.1 10.9 24.5 960 4.67 69.1 <0.5 1.2 188 0.1 3.7 <0.1 111 3.53																			
Reference Materials																					
STD DS10	Standard	14.6 146.8 148.2 330 1.8 73.0 14.1 823 2.65 49.0 54.8 7.5 60 2.8 8.1 12.6 40 1.00																			
STD DS10	Standard	15.1 154.7 148.4 353 2.0 76.7 14.3 883 2.78 43.5 55.6 7.5 69 2.7 7.0 11.7 43 1.08																			



QUALITY CONTROL REPORT

WHI16000286.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1162874	Rock	0.040	10	45	1.42	931	0.012	<20	0.86	0.040	0.32	<0.1	0.14	18.1	<0.1	<0.05	4	<0.5	<0.2
REP 1162874	QC																		
1162886	Rock	0.085	7	69	1.87	196	0.063	<20	1.97	0.038	0.81	0.1	0.03	17.5	0.2	<0.05	9	<0.5	<0.2
REP 1162886	QC	0.084	7	69	1.85	196	0.062	<20	1.95	0.037	0.81	0.1	0.03	16.8	0.2	<0.05	8	<0.5	<0.2
1162920	Rock	0.012	<1	<1	11.66	34	0.003	<20	0.04	<0.001	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2
REP 1162920	QC																		
1162921	Rock	0.056	18	28	0.92	1254	0.189	<20	1.35	0.126	0.79	2.4	<0.01	7.7	0.2	0.08	6	<0.5	<0.2
REP 1162921	QC	0.060	20	29	0.93	1221	0.194	<20	1.34	0.130	0.81	2.3	<0.01	7.9	0.1	0.08	7	<0.5	<0.2
1162948	Rock	0.052	15	39	1.29	578	0.176	<20	1.63	0.073	0.97	1.2	0.01	7.9	0.2	0.13	7	<0.5	<0.2
REP 1162948	QC																		
1184503	Rock	0.084	3	8	1.01	825	0.199	<20	1.50	0.083	0.78	0.5	0.12	9.9	0.2	<0.05	6	<0.5	<0.2
REP 1184503	QC	0.089	3	9	1.02	829	0.197	<20	1.52	0.086	0.80	0.4	0.13	10.4	0.2	<0.05	7	<0.5	<0.2
1167675	Rock	0.006	11	9	0.18	2246	<0.001	<20	0.20	0.027	0.12	2.8	2.81	3.8	<0.1	0.18	<1	2.8	5.6
REP 1167675	QC	0.006	11	9	0.18	2255	<0.001	<20	0.20	0.028	0.12	2.8	2.81	4.0	<0.1	0.19	<1	2.8	5.8
1167678	Rock	0.054	12	10	0.43	1443	0.005	<20	0.46	0.018	0.30	0.3	0.31	6.9	<0.1	0.26	2	0.5	0.7
REP 1167678	QC	0.050	11	10	0.40	1275	0.004	<20	0.43	0.017	0.28	0.3	0.29	6.5	<0.1	0.26	2	<0.5	0.7
Core Reject Duplicates																			
1162878	Rock	0.055	10	97	2.73	1781	0.032	<20	1.30	0.024	0.30	0.1	0.07	19.4	<0.1	<0.05	6	<0.5	<0.2
DUP 1162878	QC	0.056	10	94	2.65	1699	0.031	<20	1.26	0.023	0.29	0.1	0.07	18.2	<0.1	<0.05	5	<0.5	<0.2
1162912	Rock	0.042	13	24	1.41	551	0.185	<20	1.64	0.093	1.00	1.3	0.03	8.6	0.2	0.28	7	<0.5	<0.2
DUP 1162912	QC	0.047	14	26	1.50	626	0.195	<20	1.75	0.101	1.06	1.5	0.03	9.0	0.2	0.30	8	<0.5	<0.2
1162946	Rock	0.057	21	31	1.29	600	0.186	<20	1.76	0.059	1.22	1.7	0.02	6.5	0.3	0.27	7	<0.5	<0.2
DUP 1162946	QC	0.055	21	31	1.29	595	0.178	<20	1.79	0.061	1.23	1.6	0.02	6.2	0.3	0.27	7	<0.5	<0.2
1184527	Rock	0.085	5	25	0.88	772	0.008	<20	0.59	0.036	0.26	0.6	1.24	21.3	0.3	<0.05	2	<0.5	<0.2
DUP 1184527	QC	0.082	5	28	0.91	777	0.008	<20	0.64	0.046	0.28	0.5	1.23	22.7	0.3	<0.05	2	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.082	16	56	0.73	413	0.076	<20	0.95	0.064	0.30	2.9	0.29	2.9	5.3	0.28	4	2.3	4.8
STD DS10	Standard	0.071	18	58	0.78	408	0.086	<20	1.07	0.073	0.34	3.6	0.30	3.2	4.8	0.29	4	2.4	4.6



QUALITY CONTROL REPORT

WHI16000286.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			14.9	153.9	149.2	370	1.9	75.6	14.6	894	2.73	48.0	70.9	7.8	66	3.1	8.6	12.6	44	1.06
STD DS10	Standard			16.0	157.8	157.2	380	2.1	78.4	14.2	904	2.79	50.1	68.0	8.8	70	2.9	8.2	13.1	43	1.09
STD DS10	Standard			14.6	152.6	142.3	351	1.8	71.5	14.2	883	2.70	46.6	58.1	7.7	66	2.9	7.7	12.3	43	1.05
STD OREAS45EA	Standard			1.6	709.3	15.8	31	0.3	386.8	58.3	416	21.09	10.1	54.0	10.8	4	<0.1	0.3	0.3	303	0.03
STD OREAS45EA	Standard			1.6	699.7	14.4	30	0.3	410.4	57.0	409	23.07	11.2	50.1	10.1	4	<0.1	0.2	0.3	308	0.03
STD OREAS45EA	Standard			1.7	711.3	15.4	34	0.3	395.9	55.5	418	22.52	11.6	60.7	10.4	4	<0.1	0.4	0.3	302	0.03
STD OREAS45EA	Standard			1.7	739.4	16.9	36	0.3	409.0	55.0	427	24.28	12.5	59.5	12.2	4	<0.1	0.3	0.3	315	0.04
STD OREAS45EA	Standard			1.5	715.7	15.6	34	0.3	399.9	60.5	428	22.84	11.9	56.7	10.2	4	<0.1	0.3	0.3	309	0.03
STD OXD108	Standard		0.416																		
STD OXD108	Standard		0.394																		
STD OXD108	Standard		0.416																		
STD OXI121	Standard		1.823																		
STD OXI121	Standard		1.821																		
STD OXI121	Standard		1.764																		
STD OXN117	Standard		7.571																		
STD OXN117	Standard		7.423																		
STD OXN117	Standard		7.679																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		



QUALITY CONTROL REPORT

WHI16000286.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.089	18	59	0.78	418	0.082	<20	1.04	0.071	0.34	3.5	0.27	3.0	5.2	0.28	5	2.2	5.0
STD DS10	Standard	0.082	18	58	0.81	426	0.091	<20	1.08	0.072	0.35	2.9	0.30	3.4	5.3	0.28	5	1.8	4.8
STD DS10	Standard	0.079	18	56	0.76	408	0.082	<20	1.03	0.070	0.33	2.9	0.27	3.1	5.2	0.28	4	2.1	4.8
STD OREAS45EA	Standard	0.034	8	886	0.10	168	0.102	<20	3.18	0.023	0.05	<0.1	<0.01	74.7	<0.1	<0.05	12	0.6	<0.2
STD OREAS45EA	Standard	0.028	8	925	0.10	149	0.107	<20	3.50	0.022	0.06	<0.1	0.02	84.0	0.1	<0.05	13	1.3	<0.2
STD OREAS45EA	Standard	0.035	8	912	0.10	160	0.101	<20	3.29	0.025	0.06	<0.1	0.01	75.8	<0.1	<0.05	13	1.1	<0.2
STD OREAS45EA	Standard	0.030	8	920	0.10	166	0.110	<20	3.61	0.017	0.06	<0.1	<0.01	83.8	<0.1	<0.05	14	1.0	<0.2
STD OREAS45EA	Standard	0.035	8	916	0.10	167	0.106	<20	3.32	0.025	0.06	<0.1	<0.01	79.3	<0.1	<0.05	13	1.0	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000286.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.8	5.2	13.8	52	0.1	1.2	4.4	411	1.73	1.2	0.8	2.4	26	0.2	0.3	<0.1	22	0.53	
ROCK-WHI	Prep Blank	<0.005	0.9	4.3	2.1	32	<0.1	1.3	4.2	416	1.79	0.8	<0.5	2.4	22	<0.1	<0.1	<0.1	22	0.52	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 05, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000286.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.047	5	3	0.39	103	0.081	<20	0.83	0.081	0.08	<0.1	0.02	2.4	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.043	5	3	0.38	73	0.083	<20	0.83	0.087	0.09	0.1	<0.01	2.5	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: September 23, 2016
Report Date: October 06, 2016
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI16000299.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-07-22-Rock-RAB
P.O. Number
Number of Samples: 90

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Jodie Gibson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	86	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	90	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
AQ200	90	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	90	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184583	Rock	2.42	<0.005	3.0	12.3	3.8	41	<0.1	1.9	4.9	472	2.57	1.7	1.0	10.4	49	<0.1	0.2	0.2	19	0.86
1184584	Rock	2.37	<0.005	2.8	12.1	2.6	34	<0.1	2.4	4.3	399	2.15	0.9	<0.5	10.8	36	<0.1	0.1	0.1	14	0.62
1184585	Rock	2.14	<0.005	3.4	19.0	3.3	46	<0.1	7.8	6.9	591	2.87	1.8	1.7	9.3	58	<0.1	0.2	0.2	34	1.41
1184586	Rock	2.37	<0.005	3.2	7.4	3.1	43	<0.1	9.2	6.9	525	2.47	0.7	<0.5	10.9	48	<0.1	0.3	0.3	33	1.35
1184587	Rock	2.25	<0.005	2.0	5.9	3.3	46	<0.1	9.1	7.7	529	2.54	0.6	<0.5	9.7	41	<0.1	0.3	0.3	35	1.57
1184588	Rock	2.52	<0.005	3.4	5.4	5.3	47	<0.1	10.5	7.2	516	2.44	2.3	0.7	10.8	108	<0.1	0.5	0.2	27	1.76
1184589	Rock	2.23	<0.005	2.5	3.3	7.2	38	<0.1	7.1	5.7	544	2.10	4.7	1.7	10.3	150	<0.1	0.6	0.2	11	2.76
1184590	Rock	1.66	<0.005	2.4	3.8	7.2	38	<0.1	7.6	5.6	538	2.11	4.4	1.4	10.9	155	<0.1	0.6	0.2	11	2.76
1184591	Rock	1.47	0.036	7.5	4.9	7.8	30	<0.1	3.2	2.9	1659	1.63	34.3	35.1	5.5	197	0.1	0.6	<0.1	15	9.53
1184592	Rock	1.96	0.019	4.6	6.5	5.8	44	<0.1	8.0	5.4	672	2.36	10.6	8.1	10.7	61	<0.1	0.6	0.4	20	2.02
1184593	Rock	2.09	<0.005	5.3	3.7	6.2	36	<0.1	4.1	4.9	826	2.20	20.2	1.1	9.6	139	<0.1	0.5	0.9	7	4.00
1184594	Rock	2.02	<0.005	5.4	7.1	4.8	25	<0.1	1.9	3.5	474	1.52	4.6	0.8	13.0	61	<0.1	0.6	0.6	6	1.67
1184595	Rock	2.49	<0.005	3.9	10.8	3.8	34	<0.1	1.5	4.0	436	1.85	1.6	<0.5	13.6	52	<0.1	0.4	0.5	11	0.95
1184596	Rock	2.35	0.007	6.8	15.3	5.0	40	<0.1	2.1	4.7	579	2.36	11.3	7.7	12.8	90	<0.1	0.6	0.6	11	1.68
1184597	Rock	1.84	<0.005	7.0	11.6	2.7	65	<0.1	2.0	6.1	626	2.87	1.6	1.1	8.1	58	<0.1	0.1	0.2	20	1.09
1184598	Rock	2.12	<0.005	7.7	15.2	3.2	60	<0.1	2.3	5.5	528	2.72	1.9	<0.5	9.2	46	<0.1	0.2	0.3	19	0.79
1184543	Rock	1.84	0.086	3.5	6.5	6.8	65	0.3	6.3	10.4	667	3.07	2.1	80.5	4.8	134	0.1	0.5	<0.1	39	3.02
1184544	Rock	2.33	0.099	2.5	10.9	9.6	66	0.3	5.8	9.1	440	2.80	1.1	88.9	5.8	134	<0.1	0.9	<0.1	38	2.11
1184545	Rock	2.37	0.030	3.1	15.9	9.9	74	0.1	6.3	9.3	766	3.13	2.0	29.9	5.8	106	0.2	1.1	<0.1	50	2.40
1184546	Rock	2.35	0.085	25.9	18.9	34.9	78	0.4	6.8	7.6	743	2.40	3.6	87.6	7.4	121	0.3	2.8	0.2	31	2.13
1184547	Rock	2.33	0.022	8.4	34.1	30.4	53	0.1	4.1	6.4	694	2.31	4.2	24.7	9.0	135	0.2	3.5	0.2	25	2.11
1184548	Rock	2.26	0.008	1.8	11.1	7.2	60	<0.1	5.5	8.4	887	2.62	6.5	33.2	4.5	94	0.1	0.6	0.2	30	2.64
1184549	Rock	2.36	<0.005	1.1	5.5	4.3	58	<0.1	5.0	6.6	872	2.48	8.5	2.8	4.0	93	0.1	0.2	<0.1	34	2.59
1184550	Rock	0.58	<0.005	<0.1	1.1	1.4	16	<0.1	1.6	1.0	249	0.48	<0.5	<0.5	0.1	54	<0.1	<0.1	<0.1	6	20.18
1184551	Rock	2.15	0.021	2.7	4.2	7.4	52	<0.1	7.0	7.1	1057	2.55	17.9	20.5	4.4	86	0.1	0.4	0.1	34	3.72
1184552	Rock	1.98	0.011	1.6	10.0	5.6	45	<0.1	7.8	7.5	1065	2.74	2.5	8.1	7.5	106	<0.1	2.1	0.3	33	2.96
1184563	Rock	2.10	<0.005	2.2	29.7	2.3	38	<0.1	2.2	6.0	419	2.77	1.0	<0.5	9.8	69	<0.1	0.1	<0.1	16	0.86
1184564	Rock	2.55	<0.005	2.9	15.6	3.4	41	<0.1	1.3	5.7	493	2.82	0.8	1.6	9.1	86	<0.1	0.2	<0.1	22	1.28
1184565	Rock	2.29	<0.005	2.6	23.0	80.7	39	0.2	2.5	5.5	458	2.53	0.6	1.0	10.5	77	0.1	0.3	0.7	30	1.08
1184566	Rock	2.42	0.009	4.9	12.5	191.9	42	0.3	6.7	6.0	393	2.97	<0.5	6.4	9.2	82	0.2	0.4	2.9	46	1.07



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2
1184583	Rock	0.042	32	10	0.41	370	0.140	<20	1.07	0.044	0.63	1.8	0.02	3.2	0.2	0.10	6	<0.5	<0.2
1184584	Rock	0.034	32	11	0.36	332	0.115	<20	0.92	0.049	0.48	2.8	<0.01	2.6	0.2	0.11	5	<0.5	<0.2
1184585	Rock	0.066	31	32	0.72	681	0.166	<20	1.36	0.040	0.91	1.9	0.02	3.7	0.3	0.21	7	<0.5	<0.2
1184586	Rock	0.071	36	30	0.75	579	0.174	<20	1.35	0.039	1.03	1.1	0.02	3.9	0.3	0.07	7	<0.5	<0.2
1184587	Rock	0.072	33	28	0.86	330	0.177	<20	1.37	0.035	1.11	1.0	0.01	3.9	0.4	0.16	6	<0.5	<0.2
1184588	Rock	0.070	36	26	0.70	650	0.107	<20	1.04	0.035	0.76	1.0	0.03	4.1	0.3	0.16	5	<0.5	<0.2
1184589	Rock	0.062	30	14	0.42	73	0.007	<20	0.44	0.026	0.25	0.9	0.05	2.9	<0.1	0.09	2	<0.5	<0.2
1184590	Rock	0.063	31	15	0.41	73	0.008	<20	0.46	0.027	0.26	0.9	0.05	2.9	<0.1	0.09	2	<0.5	<0.2
1184591	Rock	0.017	19	9	0.09	89	0.001	<20	0.24	0.021	0.15	0.4	0.02	1.8	<0.1	<0.05	<1	<0.5	<0.2
1184592	Rock	0.053	29	19	0.29	141	0.053	<20	0.73	0.031	0.46	0.7	0.04	3.3	0.2	<0.05	3	<0.5	<0.2
1184593	Rock	0.066	30	8	0.45	107	0.003	<20	0.38	0.016	0.24	0.7	0.04	2.3	<0.1	0.11	1	<0.5	0.3
1184594	Rock	0.030	33	9	0.22	213	0.020	<20	0.53	0.033	0.26	1.4	0.03	2.0	0.1	0.13	2	<0.5	<0.2
1184595	Rock	0.037	36	10	0.30	550	0.074	<20	0.71	0.040	0.42	2.2	0.02	2.5	0.2	0.12	4	<0.5	<0.2
1184596	Rock	0.049	34	10	0.34	844	0.067	<20	0.77	0.030	0.47	1.7	0.04	3.1	0.2	0.20	4	<0.5	<0.2
1184597	Rock	0.063	29	13	0.57	408	0.160	<20	1.22	0.043	0.70	2.7	0.01	2.8	0.3	0.15	6	<0.5	<0.2
1184598	Rock	0.056	33	12	0.43	386	0.151	<20	1.08	0.043	0.69	2.3	0.02	2.7	0.2	0.12	6	<0.5	<0.2
1184543	Rock	0.032	8	9	0.51	1644	0.003	<20	0.44	0.023	0.28	0.4	0.05	10.6	<0.1	0.09	2	<0.5	0.3
1184544	Rock	0.050	12	10	0.46	2081	0.009	<20	0.42	0.034	0.28	0.6	0.02	10.4	<0.1	0.07	2	<0.5	0.3
1184545	Rock	0.047	12	11	0.52	912	0.008	<20	0.45	0.033	0.29	0.5	0.04	12.5	<0.1	<0.05	2	<0.5	<0.2
1184546	Rock	0.044	14	10	0.21	2004	0.001	<20	0.30	0.042	0.16	0.5	0.04	10.2	<0.1	0.06	1	<0.5	0.5
1184547	Rock	0.041	15	8	0.19	2634	0.002	<20	0.34	0.036	0.19	0.4	0.05	6.6	<0.1	0.07	2	<0.5	<0.2
1184548	Rock	0.029	7	9	0.78	973	0.002	<20	0.46	0.010	0.31	0.2	0.06	8.8	<0.1	<0.05	2	<0.5	<0.2
1184549	Rock	0.038	5	7	0.80	925	0.001	<20	0.38	0.017	0.24	0.2	0.05	11.5	<0.1	<0.05	1	<0.5	<0.2
1184550	Rock	0.017	<1	<1	13.23	39	<0.001	<20	0.04	0.001	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1184551	Rock	0.005	3	14	0.49	389	<0.001	<20	0.29	0.003	0.20	0.2	0.09	8.1	<0.1	<0.05	<1	<0.5	<0.2
1184552	Rock	0.047	12	14	0.75	312	0.007	<20	0.54	0.019	0.37	0.4	0.06	8.3	<0.1	<0.05	2	<0.5	<0.2
1184563	Rock	0.067	34	9	0.49	151	0.132	<20	0.97	0.076	0.48	2.5	<0.01	3.8	0.3	0.11	6	<0.5	<0.2
1184564	Rock	0.066	30	7	0.48	1357	0.119	<20	1.04	0.047	0.56	1.6	<0.01	4.2	0.3	0.07	7	<0.5	<0.2
1184565	Rock	0.048	32	10	0.33	411	0.100	<20	0.67	0.074	0.33	2.6	<0.01	4.4	0.2	0.08	4	<0.5	<0.2
1184566	Rock	0.075	31	23	0.68	1649	0.118	<20	1.03	0.055	0.57	1.3	<0.01	5.3	0.2	0.06	6	<0.5	0.8



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184567	Rock	2.38	<0.005	2.4	3.6	2.2	31	<0.1	9.9	6.2	355	2.48	<0.5	0.6	8.7	49	<0.1	0.3	0.2	45	1.17
1184568	Rock	2.73	<0.005	2.2	3.5	1.8	32	<0.1	10.4	6.7	306	2.57	0.7	2.2	8.1	36	<0.1	0.2	0.2	48	0.75
1184569	Rock	2.22	<0.005	2.3	5.3	1.3	28	<0.1	9.7	6.5	303	2.63	0.7	<0.5	7.8	37	<0.1	0.2	0.9	42	0.55
1184570	Rock Pulp	0.11	0.945	4.3	36.5	5.6	50	0.4	24.1	9.6	387	2.46	6.4	544.8	1.0	38	0.3	0.9	0.1	57	0.77
1184571	Rock	2.48	<0.005	2.3	5.8	2.1	28	<0.1	9.2	6.1	309	2.48	0.5	<0.5	7.8	47	<0.1	0.6	0.2	32	1.21
1184572	Rock	2.26	<0.005	1.9	3.9	1.3	29	<0.1	9.6	6.4	293	2.56	<0.5	<0.5	7.1	33	<0.1	0.2	<0.1	38	0.61
1184553	Rock	2.12	0.007	2.0	9.9	3.4	42	<0.1	10.9	6.4	733	2.34	2.2	3.6	9.2	133	<0.1	0.4	0.1	38	2.25
1184554	Rock	2.18	<0.005	4.9	16.5	10.0	51	<0.1	15.2	7.8	771	2.73	0.8	0.9	9.4	123	0.1	0.6	0.2	48	1.71
1184555	Rock	1.95	<0.005	3.3	16.1	7.8	75	<0.1	6.7	5.4	513	1.93	2.1	2.6	12.6	71	0.1	0.6	0.2	22	1.22
1184556	Rock	2.39	0.011	3.4	10.2	6.1	38	<0.1	3.3	5.7	728	2.18	0.8	6.5	11.8	72	0.1	0.5	0.2	17	1.64
1184557	Rock	2.23	0.015	8.3	23.0	16.2	53	0.1	4.3	6.3	811	2.52	3.1	12.6	9.5	97	0.2	1.4	0.2	24	1.99
1184558	Rock	1.49	0.014	4.0	33.1	15.9	47	<0.1	4.5	6.9	886	2.69	8.9	10.7	7.6	121	0.3	1.5	0.2	25	3.86
1184559	Rock	2.82	0.006	2.3	37.7	7.6	47	<0.1	1.2	6.5	708	3.53	1.9	3.9	11.1	105	0.1	1.0	0.3	16	2.19
1184560	Rock	2.09	0.005	2.5	36.6	7.5	47	<0.1	1.6	7.0	695	3.53	1.8	3.9	11.2	105	0.1	1.0	0.3	16	2.13
1184561	Rock	2.29	<0.005	1.9	13.1	2.4	58	<0.1	1.0	6.3	594	3.16	0.5	<0.5	8.8	85	<0.1	0.2	<0.1	23	1.15
1184562	Rock	2.36	<0.005	2.5	16.9	2.0	44	<0.1	1.9	5.3	453	2.68	0.9	0.8	9.7	63	<0.1	0.2	0.1	19	0.88
1184533	Rock	1.39	3.256	2.8	29.3	5.3	47	0.7	12.3	8.3	640	2.43	21.7	2451.2	2.9	61	0.2	4.8	0.2	38	0.54
1184534	Rock	1.31	1.704	3.1	21.5	5.2	44	0.4	5.4	9.4	732	3.11	19.3	1856.5	2.7	37	0.1	4.6	0.3	38	0.17
1184535	Rock	2.18	4.333	2.3	14.6	4.8	27	0.7	4.6	6.5	590	2.14	9.3	3220.9	1.9	40	<0.1	2.9	0.2	16	0.11
1184536	Rock	2.07	5.318	13.8	26.8	55.9	47	4.9	6.1	8.5	615	2.80	13.0	29121.3	1.1	55	0.2	5.3	0.3	16	1.05
1184537	Rock	2.00	0.271	3.8	23.3	5.2	62	0.2	7.9	10.6	784	3.53	3.9	212.4	3.1	123	0.2	1.8	<0.1	41	3.79
1184538	Rock	2.40	0.094	1.6	15.0	4.5	82	0.2	9.2	11.5	762	3.41	6.3	74.0	3.8	132	0.3	0.9	<0.1	45	3.08
1184539	Rock	2.18	0.088	2.9	25.1	4.8	74	0.3	9.1	11.3	557	3.57	7.0	74.4	3.8	121	0.2	0.8	0.1	42	2.15
1184540	Rock Pulp	0.11	2.150	66.9	2158.3	1262.0	3630	25.9	176.0	21.1	632	5.18	1176.1	1081.2	2.5	69	21.7	16.6	10.0	55	1.47
1184541	Rock	2.46	0.144	2.3	9.6	8.5	69	0.5	5.2	9.3	347	2.79	5.2	155.2	4.9	77	<0.1	1.5	0.1	29	1.55
1184542	Rock	2.19	0.305	11.0	7.9	21.2	86	1.1	8.5	12.6	444	3.25	2.0	328.2	7.1	105	0.1	0.8	0.2	38	1.19
1184573	Rock	2.29	<0.005	2.1	4.1	2.2	38	<0.1	9.0	7.0	405	2.36	<0.5	<0.5	8.2	39	<0.1	0.2	0.4	35	0.81
1184574	Rock	2.46	<0.005	2.1	16.6	3.2	36	<0.1	8.7	6.6	382	2.50	0.7	1.6	11.9	63	<0.1	0.4	0.1	32	1.09
1184575	Rock	2.04	<0.005	2.1	11.2	3.1	27	<0.1	5.7	4.4	329	1.96	0.9	0.6	11.1	52	<0.1	0.4	0.3	22	1.14
1184576	Rock	2.33	<0.005	2.7	21.4	5.4	32	<0.1	2.1	4.9	426	2.18	1.1	1.1	10.3	81	<0.1	0.5	0.9	15	1.64



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1184567	Rock	0.080	30	32	0.87	503	0.151	<20	1.27	0.067	0.70	1.4	<0.01	4.3	0.2	<0.05	7	<0.5	<0.2
1184568	Rock	0.087	26	34	0.93	522	0.186	<20	1.39	0.069	0.77	1.9	<0.01	4.7	0.3	0.05	8	<0.5	<0.2
1184569	Rock	0.078	29	29	0.85	718	0.207	<20	1.42	0.059	0.92	1.6	<0.01	3.2	0.3	0.06	8	<0.5	0.6
1184570	Rock Pulp	0.062	4	32	0.71	96	0.115	<20	1.43	0.080	0.13	11.7	0.05	4.3	<0.1	<0.05	5	<0.5	<0.2
1184571	Rock	0.084	25	22	0.87	448	0.134	<20	1.24	0.035	0.74	1.1	0.02	2.6	0.3	0.11	7	<0.5	<0.2
1184572	Rock	0.075	26	27	0.82	502	0.186	<20	1.34	0.044	0.90	1.3	0.02	2.3	0.3	0.05	7	<0.5	<0.2
1184553	Rock	0.060	23	29	0.56	427	0.056	<20	0.66	0.038	0.51	0.9	0.01	7.9	0.1	<0.05	4	<0.5	<0.2
1184554	Rock	0.064	25	36	0.67	888	0.082	<20	0.91	0.041	0.62	0.7	0.03	8.5	0.2	<0.05	5	<0.5	<0.2
1184555	Rock	0.039	29	16	0.30	523	0.037	<20	0.52	0.042	0.36	0.6	<0.01	5.4	0.1	<0.05	3	<0.5	<0.2
1184556	Rock	0.044	29	11	0.22	309	0.042	<20	0.49	0.032	0.39	0.6	<0.01	7.2	0.2	<0.05	3	<0.5	<0.2
1184557	Rock	0.057	20	12	0.15	1028	0.022	<20	0.39	0.034	0.27	0.5	<0.01	7.4	0.1	<0.05	2	<0.5	<0.2
1184558	Rock	0.065	21	9	0.14	1256	0.009	<20	0.40	0.027	0.24	0.2	0.08	8.3	0.2	<0.05	2	<0.5	<0.2
1184559	Rock	0.081	40	5	0.56	478	0.105	<20	1.18	0.026	0.83	0.4	0.02	6.0	0.4	<0.05	6	<0.5	<0.2
1184560	Rock	0.077	40	6	0.55	502	0.105	<20	1.16	0.029	0.82	0.4	0.02	5.7	0.3	<0.05	7	<0.5	<0.2
1184561	Rock	0.070	30	6	0.43	324	0.098	<20	0.85	0.056	0.43	0.8	<0.01	5.4	0.2	<0.05	6	<0.5	<0.2
1184562	Rock	0.054	32	9	0.36	144	0.107	<20	0.84	0.062	0.42	1.2	<0.01	4.0	0.2	<0.05	5	<0.5	<0.2
1184533	Rock	0.039	11	18	0.17	1163	0.007	<20	0.37	0.019	0.16	0.8	0.56	9.2	<0.1	<0.05	1	<0.5	0.3
1184534	Rock	0.050	8	8	0.09	728	0.001	<20	0.39	0.014	0.25	0.4	0.43	12.2	<0.1	<0.05	1	<0.5	0.2
1184535	Rock	0.027	6	8	0.06	428	<0.001	<20	0.23	0.011	0.14	0.9	0.41	8.0	<0.1	<0.05	<1	<0.5	0.3
1184536	Rock	0.008	2	10	0.07	1318	<0.001	<20	0.21	0.003	0.13	0.7	0.71	10.3	0.1	<0.05	<1	<0.5	0.8
1184537	Rock	0.039	10	9	0.72	964	0.001	<20	0.38	0.021	0.21	2.1	0.24	12.5	<0.1	<0.05	1	<0.5	0.2
1184538	Rock	0.026	10	15	1.00	873	0.002	<20	0.37	0.023	0.23	0.4	0.12	13.4	<0.1	<0.05	1	<0.5	0.2
1184539	Rock	0.016	7	22	0.57	686	0.002	<20	0.45	0.018	0.29	0.2	0.19	12.6	<0.1	<0.05	2	<0.5	0.2
1184540	Rock Pulp	0.066	11	45	0.84	206	0.085	<20	1.48	0.082	0.19	9.3	0.69	4.0	1.3	1.52	6	3.3	0.5
1184541	Rock	0.027	12	7	0.30	380	0.002	<20	0.35	0.025	0.22	0.3	0.08	11.9	<0.1	<0.05	1	<0.5	0.4
1184542	Rock	0.051	16	11	0.19	1609	0.003	<20	0.34	0.047	0.18	0.3	0.07	12.5	<0.1	0.05	2	<0.5	0.8
1184573	Rock	0.077	26	25	0.77	423	0.185	<20	1.34	0.045	0.94	1.5	<0.01	2.4	0.4	<0.05	6	<0.5	0.3
1184574	Rock	0.058	33	23	0.63	1194	0.140	<20	1.23	0.044	0.81	1.2	0.01	3.6	0.3	0.08	6	<0.5	<0.2
1184575	Rock	0.048	33	17	0.44	461	0.110	<20	1.01	0.042	0.61	1.4	0.03	2.7	0.2	<0.05	6	<0.5	<0.2
1184576	Rock	0.040	34	10	0.29	778	0.073	<20	0.84	0.038	0.41	1.3	0.01	3.6	0.1	0.14	5	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 4 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184577	Rock	2.18	<0.005	3.1	11.0	3.9	35	<0.1	1.5	5.0	483	2.23	<0.5	0.7	11.1	55	<0.1	0.4	1.9	16	1.48
1184578	Rock	2.35	<0.005	2.5	7.7	4.3	54	<0.1	2.3	5.7	605	2.80	0.8	0.8	10.3	53	<0.1	0.5	0.3	23	1.46
1184579	Rock	2.64	<0.005	2.1	8.5	3.2	51	<0.1	1.5	5.2	528	2.53	<0.5	0.7	9.0	46	<0.1	0.2	0.2	20	0.81
1184580	Rock	0.75	<0.005	<0.1	1.1	138.8	13	<0.1	2.3	1.1	217	0.50	<0.5	<0.5	7.7	49	<0.1	<0.1	<0.1	8	19.09
1184581	Rock	2.42	<0.005	2.6	19.0	4.1	42	<0.1	1.4	4.9	480	2.60	0.7	<0.5	10.8	65	<0.1	0.4	0.3	18	1.03
1184582	Rock	2.29	<0.005	2.6	15.1	3.2	45	<0.1	1.4	4.9	509	2.58	<0.5	<0.5	10.3	54	<0.1	0.3	0.2	19	0.95
1184599	Rock	1.61	0.733	3.2	23.6	5.3	53	0.6	14.9	9.4	779	2.90	22.2	1120.4	2.6	52	0.2	4.3	0.3	45	0.41
1184600	Rock Pulp	0.11	2.026	65.0	2196.7	1273.0	3714	26.4	183.2	21.8	641	5.20	1193.6	1138.5	2.6	73	22.0	17.2	10.2	55	1.48
1184601	Rock	1.39	1.661	4.9	20.8	5.3	53	0.5	6.8	10.7	857	3.11	17.7	1395.3	2.2	42	0.2	3.8	0.3	32	0.10
1184602	Rock	2.30	3.285	20.4	26.4	19.1	41	1.0	7.0	9.9	725	2.85	13.0	3198.6	2.5	66	0.1	6.1	1.0	29	0.15
1184603	Rock	1.53	2.249	6.0	14.2	5.8	40	0.6	3.3	9.3	933	2.88	7.6	3766.7	3.1	59	<0.1	3.1	0.4	31	0.16
1184604	Rock	1.65	0.689	5.3	16.8	5.0	54	0.3	3.2	12.3	1261	3.45	11.6	897.5	2.3	63	0.1	4.1	0.3	40	0.15
1184605	Rock	2.19	3.261	7.1	31.7	4.9	43	0.5	4.0	9.7	1008	2.83	13.7	2158.7	1.5	75	0.1	6.0	0.3	24	2.22
1184606	Rock	2.21	7.994	25.4	29.8	6.3	34	0.6	3.1	6.6	755	2.31	6.6	2323.3	1.2	105	0.1	7.8	0.3	10	2.99
1184607	Rock	2.27	0.736	44.5	23.4	19.5	57	0.5	4.3	7.7	783	2.78	6.4	745.1	1.9	126	0.3	6.3	0.3	15	3.22
1184608	Rock	1.96	0.344	25.1	14.4	27.6	67	0.7	9.9	12.0	683	2.34	14.9	364.3	1.6	72	0.3	2.0	0.5	23	1.29
1184619	Rock	2.40	0.082	2.0	19.8	7.4	81	0.3	5.8	11.1	757	3.35	3.1	82.8	5.2	132	0.3	1.3	0.1	49	2.04
1184620	Rock	0.61	0.011	0.2	1.7	1.6	13	<0.1	1.6	0.9	209	0.44	<0.5	0.5	0.9	55	<0.1	<0.1	<0.1	6	19.58
1184621	Rock	2.38	0.024	1.7	9.6	7.3	59	<0.1	6.5	10.5	1091	3.05	1.8	11.9	5.6	193	0.2	0.7	0.1	50	3.09
1184622	Rock	2.09	0.026	2.0	10.9	6.0	47	<0.1	6.2	8.4	858	2.71	2.5	30.5	6.8	170	0.1	0.8	<0.1	32	2.51
1184609	Rock	2.15	0.152	10.6	10.0	7.1	65	0.3	5.8	8.9	763	2.95	11.6	164.3	2.2	108	0.3	1.9	<0.1	26	2.35
1184610	Rock Pulp	0.11	0.894	4.6	35.3	5.6	52	0.3	25.6	10.1	412	2.55	6.8	979.5	1.0	40	0.1	1.0	0.1	63	0.85
1184611	Rock	2.23	0.203	4.6	12.3	6.2	65	0.6	5.8	9.4	721	3.03	6.1	323.4	2.1	105	0.4	2.6	0.1	24	1.99
1184612	Rock	2.28	0.437	8.1	29.9	7.3	61	1.0	6.0	9.1	693	3.10	9.5	393.4	2.5	102	0.5	5.6	0.2	31	2.29
1184613	Rock	2.14	0.081	2.6	13.2	5.5	60	0.2	5.9	9.0	624	2.75	11.7	61.5	2.7	99	0.2	1.7	0.1	30	1.87
1184614	Rock	2.37	0.096	4.3	14.9	8.4	63	0.2	7.4	10.9	899	3.22	14.0	65.9	2.3	131	0.2	2.1	0.1	34	2.72
1184615	Rock	2.31	0.032	4.0	9.9	5.3	55	<0.1	6.0	8.8	727	2.98	9.5	41.0	2.6	87	0.2	1.6	0.1	29	1.99
1184616	Rock	1.91	0.038	3.4	9.4	5.1	55	0.1	5.6	8.7	688	2.96	8.0	32.0	2.7	74	0.2	1.3	0.1	27	1.59
1184617	Rock	2.32	0.023	2.8	11.5	6.5	49	<0.1	6.3	9.0	792	2.53	5.8	13.8	2.3	90	0.2	1.3	0.1	26	2.11
1184618	Rock	2.37	0.045	2.8	29.1	8.0	82	0.1	6.4	9.6	1169	3.55	5.4	39.1	3.8	164	0.3	1.8	<0.1	46	3.41



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000299.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1184577	Rock	0.039	37	8	0.36	407	0.106	<20	0.94	0.042	0.59	1.3	0.02	3.8	0.2	0.11	5	<0.5	0.5
1184578	Rock	0.054	34	11	0.45	454	0.161	<20	1.19	0.038	0.85	1.1	0.02	4.9	0.3	0.09	7	<0.5	<0.2
1184579	Rock	0.048	34	9	0.45	334	0.157	<20	1.14	0.040	0.77	1.7	0.01	3.1	0.2	0.08	6	<0.5	<0.2
1184580	Rock	0.017	<1	<1	12.68	71	0.008	<20	0.23	0.002	0.18	<0.1	<0.01	0.2	0.1	<0.05	<1	<0.5	<0.2
1184581	Rock	0.046	34	10	0.40	628	0.127	<20	1.02	0.037	0.67	1.6	0.03	3.6	0.2	0.17	6	<0.5	<0.2
1184582	Rock	0.047	33	9	0.44	525	0.123	<20	1.03	0.042	0.61	1.7	<0.01	3.3	0.2	0.16	6	<0.5	<0.2
1184599	Rock	0.037	9	21	0.15	776	0.002	<20	0.35	0.019	0.19	1.0	0.71	10.6	<0.1	<0.05	1	<0.5	0.4
1184600	Rock Pulp	0.066	11	46	0.85	202	0.087	<20	1.48	0.082	0.19	8.4	0.73	3.9	1.3	1.52	6	3.6	0.5
1184601	Rock	0.021	6	10	0.08	1502	<0.001	<20	0.36	0.005	0.25	0.5	0.60	11.5	0.1	<0.05	1	<0.5	0.4
1184602	Rock	0.040	8	11	0.08	1201	0.001	<20	0.35	0.015	0.22	1.2	0.68	10.2	<0.1	<0.05	1	<0.5	1.2
1184603	Rock	0.040	8	6	0.08	1546	0.001	<20	0.35	0.013	0.25	0.5	0.39	12.2	<0.1	<0.05	1	<0.5	0.2
1184604	Rock	0.038	7	6	0.11	988	0.001	<20	0.43	0.012	0.28	0.4	0.40	18.2	0.1	<0.05	1	<0.5	<0.2
1184605	Rock	0.011	5	5	0.10	615	<0.001	<20	0.34	0.004	0.24	0.4	0.79	14.0	<0.1	<0.05	1	<0.5	0.2
1184606	Rock	0.009	3	5	0.09	1522	<0.001	<20	0.23	0.003	0.16	0.7	0.88	10.3	<0.1	<0.05	<1	<0.5	0.3
1184607	Rock	0.006	2	4	0.11	1785	<0.001	<20	0.23	0.003	0.15	0.4	0.29	8.2	0.2	<0.05	<1	<0.5	0.4
1184608	Rock	0.004	3	10	0.28	318	<0.001	<20	0.29	0.003	0.16	0.2	0.42	10.8	0.2	<0.05	<1	<0.5	1.1
1184619	Rock	0.070	11	9	0.76	1055	0.006	<20	0.42	0.028	0.27	0.4	0.06	14.1	<0.1	0.07	2	<0.5	0.2
1184620	Rock	0.018	<1	<1	12.93	33	0.001	<20	0.05	0.001	0.03	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2
1184621	Rock	0.054	10	15	1.09	1957	0.005	<20	0.46	0.026	0.30	0.3	0.06	13.3	<0.1	0.08	2	<0.5	<0.2
1184622	Rock	0.055	12	14	1.01	1227	0.009	<20	0.55	0.021	0.38	0.3	0.06	12.3	0.1	0.09	3	<0.5	<0.2
1184609	Rock	0.005	5	7	0.52	1500	<0.001	<20	0.27	0.003	0.17	0.2	0.34	11.4	0.1	<0.05	<1	<0.5	0.4
1184610	Rock Pulp	0.058	5	33	0.74	99	0.131	<20	1.57	0.090	0.14	11.3	0.05	4.8	<0.1	<0.05	5	<0.5	<0.2
1184611	Rock	0.008	5	6	0.43	1442	<0.001	<20	0.26	0.002	0.17	0.3	0.27	12.1	<0.1	<0.05	<1	<0.5	0.5
1184612	Rock	0.008	4	7	0.35	1137	<0.001	<20	0.28	0.002	0.19	0.2	0.47	11.5	0.1	<0.05	<1	<0.5	0.9
1184613	Rock	0.008	4	7	0.31	1042	<0.001	<20	0.29	0.001	0.21	0.2	0.28	10.0	<0.1	<0.05	<1	<0.5	<0.2
1184614	Rock	0.020	5	12	0.44	1485	<0.001	<20	0.27	0.002	0.18	0.3	0.29	10.7	0.1	<0.05	<1	<0.5	<0.2
1184615	Rock	0.009	3	7	0.25	846	<0.001	<20	0.27	0.002	0.19	0.2	0.18	11.9	0.1	<0.05	<1	<0.5	<0.2
1184616	Rock	0.004	3	7	0.20	680	<0.001	<20	0.27	0.002	0.19	0.3	0.21	12.1	0.1	<0.05	1	<0.5	<0.2
1184617	Rock	0.003	4	8	0.28	893	<0.001	<20	0.30	0.002	0.21	0.2	0.20	11.3	0.1	<0.05	1	<0.5	<0.2
1184618	Rock	0.024	8	9	0.92	1930	<0.001	<20	0.34	0.018	0.19	0.2	0.31	13.8	<0.1	0.06	1	<0.5	<0.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 1 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000299.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1184567	Rock	2.38	<0.005	2.4	3.6	2.2	31	<0.1	9.9	6.2	355	2.48	<0.5	0.6	8.7	49	<0.1	0.3	0.2	45	1.17
REP 1184567	QC			2.8	3.6	2.3	31	<0.1	10.6	6.2	365	2.57	<0.5	0.9	8.5	50	<0.1	0.3	0.2	45	1.21
1184553	Rock	2.12	0.007	2.0	9.9	3.4	42	<0.1	10.9	6.4	733	2.34	2.2	3.6	9.2	133	<0.1	0.4	0.1	38	2.25
REP 1184553	QC		0.006																		
1184582	Rock	2.29	<0.005	2.6	15.1	3.2	45	<0.1	1.4	4.9	509	2.58	<0.5	<0.5	10.3	54	<0.1	0.3	0.2	19	0.95
REP 1184582	QC			2.9	15.2	3.2	45	<0.1	1.6	5.2	505	2.56	0.5	<0.5	9.8	53	<0.1	0.3	0.2	19	0.94
1184617	Rock	2.32	0.023	2.8	11.5	6.5	49	<0.1	6.3	9.0	792	2.53	5.8	13.8	2.3	90	0.2	1.3	0.1	26	2.11
REP 1184617	QC		0.023	3.1	12.2	6.9	52	<0.1	6.4	9.4	837	2.67	6.2	20.7	2.5	94	0.2	1.3	<0.1	27	2.22
Core Reject Duplicates																					
1184544	Rock	2.33	0.099	2.5	10.9	9.6	66	0.3	5.8	9.1	440	2.80	1.1	88.9	5.8	134	<0.1	0.9	<0.1	38	2.11
DUP 1184544	QC		0.091	2.9	12.4	10.5	72	0.3	6.8	10.1	468	3.04	1.0	86.0	6.3	143	<0.1	0.8	<0.1	41	2.25
1184538	Rock	2.40	0.094	1.6	15.0	4.5	82	0.2	9.2	11.5	762	3.41	6.3	74.0	3.8	132	0.3	0.9	<0.1	45	3.08
DUP 1184538	QC		0.094	1.3	15.2	4.5	87	0.2	9.4	11.3	755	3.41	6.6	76.7	3.7	128	0.3	0.9	<0.1	44	3.04
1184614	Rock	2.37	0.096	4.3	14.9	8.4	63	0.2	7.4	10.9	899	3.22	14.0	65.9	2.3	131	0.2	2.1	0.1	34	2.72
DUP 1184614	QC		0.077	3.9	15.2	8.1	65	0.2	7.0	11.0	876	3.23	13.8	62.9	2.5	126	0.2	2.0	0.1	34	2.66
Reference Materials																					
STD DS10	Standard			14.4	166.3	153.1	357	2.0	79.5	14.5	919	2.89	47.6	100.3	7.5	67	2.8	9.0	12.1	46	1.13
STD DS10	Standard			13.8	173.1	146.8	353	1.8	77.9	13.9	884	2.77	43.1	117.1	7.6	62	2.8	8.8	11.7	44	1.05
STD DS10	Standard			14.5	164.8	146.5	362	1.9	77.9	14.0	890	2.76	43.4	54.9	7.2	61	2.7	8.4	12.4	44	1.06
STD OREAS45EA	Standard			1.8	749.0	15.0	31	0.3	413.8	57.8	443	23.17	11.8	61.0	10.5	4	<0.1	0.4	0.3	320	0.03
STD OREAS45EA	Standard			1.7	712.4	14.8	29	0.3	391.2	56.4	425	22.92	10.2	62.2	10.5	4	<0.1	0.3	0.2	307	0.03
STD OREAS45EA	Standard			2.0	735.4	16.1	30	0.3	403.2	57.6	428	21.94	10.8	48.8	11.3	4	<0.1	0.4	0.3	311	0.03
STD OXD108	Standard		0.416																		
STD OXD108	Standard		0.418																		
STD OXI121	Standard		1.764																		
STD OXI121	Standard		1.752																		
STD OXN117	Standard		7.679																		
STD OXN117	Standard		7.509																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000299.1

Method		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1184567	Rock	0.080	30	32	0.87	503	0.151	<20	1.27	0.067	0.70	1.4	<0.01	4.3	0.2	<0.05	7	<0.5	<0.2
REP 1184567	QC	0.082	30	33	0.89	513	0.153	<20	1.28	0.068	0.72	1.4	<0.01	4.3	0.2	<0.05	8	<0.5	<0.2
1184553	Rock	0.060	23	29	0.56	427	0.056	<20	0.66	0.038	0.51	0.9	0.01	7.9	0.1	<0.05	4	<0.5	<0.2
REP 1184553	QC																		
1184582	Rock	0.047	33	9	0.44	525	0.123	<20	1.03	0.042	0.61	1.7	<0.01	3.3	0.2	0.16	6	<0.5	<0.2
REP 1184582	QC	0.044	32	10	0.44	524	0.122	<20	1.03	0.041	0.61	1.7	0.01	3.2	0.2	0.16	6	<0.5	<0.2
1184617	Rock	0.003	4	8	0.28	893	<0.001	<20	0.30	0.002	0.21	0.2	0.20	11.3	0.1	<0.05	1	<0.5	<0.2
REP 1184617	QC	0.003	4	8	0.29	899	<0.001	<20	0.31	0.002	0.21	0.2	0.23	11.8	0.1	<0.05	1	<0.5	<0.2
Core Reject Duplicates																			
1184544	Rock	0.050	12	10	0.46	2081	0.009	<20	0.42	0.034	0.28	0.6	0.02	10.4	<0.1	0.07	2	<0.5	0.3
DUP 1184544	QC	0.051	13	12	0.49	2194	0.010	<20	0.47	0.039	0.30	0.5	0.02	11.2	0.1	0.08	2	<0.5	0.3
1184538	Rock	0.026	10	15	1.00	873	0.002	<20	0.37	0.023	0.23	0.4	0.12	13.4	<0.1	<0.05	1	<0.5	0.2
DUP 1184538	QC	0.026	10	15	0.98	862	0.002	<20	0.37	0.025	0.23	0.4	0.15	12.6	<0.1	<0.05	1	<0.5	0.2
1184614	Rock	0.020	5	12	0.44	1485	<0.001	<20	0.27	0.002	0.18	0.3	0.29	10.7	0.1	<0.05	<1	<0.5	<0.2
DUP 1184614	QC	0.017	6	11	0.43	1396	<0.001	<20	0.26	0.001	0.18	0.3	0.29	10.6	0.1	<0.05	<1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.083	18	59	0.81	422	0.082	<20	1.07	0.075	0.35	3.1	0.36	2.9	5.1	0.30	4	2.2	4.9
STD DS10	Standard	0.078	17	56	0.77	409	0.082	<20	1.04	0.073	0.33	2.9	0.28	2.8	5.0	0.28	4	1.9	4.9
STD DS10	Standard	0.078	17	56	0.78	393	0.081	<20	1.05	0.073	0.34	3.0	0.28	2.8	4.9	0.28	4	2.3	4.9
STD OREAS45EA	Standard	0.033	7	929	0.10	140	0.105	<20	3.37	0.026	0.06	<0.1	<0.01	78.1	<0.1	<0.05	13	1.0	<0.2
STD OREAS45EA	Standard	0.031	7	885	0.09	143	0.099	<20	3.17	0.025	0.05	<0.1	0.01	75.3	<0.1	<0.05	13	0.6	<0.2
STD OREAS45EA	Standard	0.031	8	891	0.10	151	0.103	<20	3.43	0.025	0.06	<0.1	0.01	75.9	<0.1	<0.05	13	1.0	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000299.1

	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD OXD108 Expected	0.414																				
STD OXN117 Expected	7.679																				
STD OXI121 Expected	1.834																				
STD DS10 Expected			13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected			1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.8	3.3	1.5	30	<0.1	0.6	3.8	404	1.65	0.9	0.9	2.4	24	<0.1	<0.1	<0.1	22	0.57	
ROCK-WHI	Prep Blank	<0.005	0.8	4.0	1.3	33	<0.1	0.7	4.0	415	1.70	0.8	<0.5	2.6	25	<0.1	<0.1	<0.1	22	0.58	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 06, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000299.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
Prep Wash																				
ROCK-WHI	Prep Blank	0.041	5	2	0.38	63	0.073	<20	0.83	0.058	0.07	0.1	<0.01	2.0	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.046	5	2	0.39	66	0.080	<20	0.84	0.059	0.07	0.1	<0.01	2.2	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: October 06, 2016
Report Date: October 28, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000356.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-10-06
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	138	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456533	Rock	1.89	<0.005	1.9	15.4	9.6	32	<0.1	10.1	5.3	493	2.18	7.5	3.1	13.9	67	0.1	0.6	0.4	16	0.92
1456534	Rock	1.82	<0.005	1.8	5.6	11.9	24	<0.1	4.1	3.2	300	1.78	2.9	<0.5	7.6	69	<0.1	0.3	0.2	8	0.96
1456535	Rock	1.97	<0.005	1.8	6.3	9.1	28	<0.1	3.6	3.3	353	1.94	2.2	<0.5	9.0	77	<0.1	0.3	0.1	8	1.24
1456536	Rock	1.64	<0.005	1.3	15.7	9.9	58	<0.1	14.7	7.4	556	2.67	2.1	<0.5	11.6	60	<0.1	0.4	0.1	20	2.16
1456537	Rock	1.69	<0.005	1.4	6.9	10.2	25	<0.1	4.1	2.9	325	1.61	1.7	<0.5	11.4	64	<0.1	0.5	0.2	8	0.65
1456538	Rock	2.53	<0.005	2.1	15.1	14.0	34	<0.1	3.1	4.5	663	2.25	7.8	<0.5	11.9	58	0.1	1.0	0.6	10	0.13
1456539	Rock	1.94	<0.005	2.4	14.3	24.9	28	<0.1	2.9	5.5	558	2.51	13.1	<0.5	6.7	91	<0.1	1.3	1.0	12	0.16
1456540	Rock Pulp	0.12	2.110	55.8	2109.5	1282.9	3688	24.8	181.1	19.7	626	5.06	1133.0	2170.3	2.6	75	22.7	16.6	10.4	57	1.46
1456541	Rock	0.91	0.011	2.3	14.7	15.1	34	<0.1	4.2	5.4	608	2.25	4.3	1.9	9.5	78	0.1	1.2	0.3	11	1.17
1456542	Rock	1.53	0.019	1.8	8.7	8.0	23	<0.1	2.4	3.2	449	1.66	2.0	30.2	14.0	92	<0.1	0.4	0.2	7	1.55
1456543	Rock	2.87	0.085	2.1	12.1	6.1	35	<0.1	2.4	4.5	589	2.48	2.2	21.4	9.6	92	0.1	0.4	0.1	15	2.28
1456544	Rock	1.34	0.012	2.8	7.4	9.4	48	<0.1	2.1	5.5	974	3.05	5.0	6.0	5.3	123	0.1	0.3	0.1	16	2.78
1456545	Rock	1.62	0.013	2.3	10.7	13.5	41	<0.1	3.1	5.9	470	2.99	7.2	1.4	4.9	125	<0.1	0.3	0.3	8	1.50
1456546	Rock	1.63	0.012	1.6	8.8	7.6	29	<0.1	4.0	5.0	553	2.02	1.9	4.4	11.1	74	<0.1	0.3	0.2	9	1.79
1456547	Rock	2.17	0.007	2.8	17.4	6.5	32	<0.1	7.9	6.5	682	2.23	2.4	6.9	15.9	60	<0.1	0.6	0.2	15	1.12
1456548	Rock	1.42	0.006	2.2	11.1	5.6	31	<0.1	2.7	4.0	460	2.19	2.7	4.0	12.6	103	<0.1	0.4	0.2	6	1.93
1419684	Rock	2.49	0.006	1.7	7.0	6.3	46	<0.1	2.9	3.0	496	2.60	3.6	1.2	12.3	16	0.1	0.3	0.5	10	0.19
1419685	Rock	2.88	0.015	2.6	19.4	6.9	34	<0.1	3.0	3.9	395	2.29	4.0	13.2	15.2	35	<0.1	0.5	0.4	8	0.14
1419686	Rock	3.17	0.008	2.7	21.1	12.7	33	<0.1	2.5	4.5	629	2.76	53.8	5.7	5.1	36	0.1	0.7	0.8	6	0.18
1419687	Rock	3.48	0.007	1.2	8.9	10.3	49	<0.1	2.1	4.0	508	2.88	16.2	6.2	10.4	100	0.1	0.6	0.9	6	1.18
1419688	Rock	1.16	0.011	1.7	26.0	9.7	36	<0.1	1.7	3.8	548	2.45	7.0	7.8	12.7	33	<0.1	0.8	0.5	4	0.45
1419689	Rock	2.22	0.008	1.3	15.1	5.7	37	<0.1	1.8	4.3	496	2.50	4.1	14.2	15.6	28	<0.1	0.5	0.5	7	0.18
1419690	Rock	2.52	0.007	1.3	15.7	5.9	37	<0.1	1.7	4.2	500	2.46	4.4	4.8	15.1	27	<0.1	0.5	0.6	7	0.16
1419691	Rock	1.82	<0.005	1.7	18.6	7.2	47	<0.1	3.1	4.9	403	2.70	11.7	<0.5	13.7	33	0.1	0.4	0.9	14	0.25
1419692	Rock	1.57	0.009	1.6	14.9	5.6	42	<0.1	4.6	6.6	547	2.98	18.5	6.0	12.0	34	0.1	0.7	0.4	32	0.26
1419693	Rock	1.56	0.012	2.6	35.2	8.5	52	<0.1	2.0	5.6	873	3.53	27.5	11.2	12.5	37	0.2	0.8	0.6	24	0.20
1456504	Rock	1.92	0.369	23.0	55.2	10.7	23	0.4	3.1	4.1	557	1.96	15.4	281.7	6.7	181	0.2	7.3	0.1	8	2.23
1456505	Rock	1.19	0.974	22.4	32.5	10.4	19	0.4	3.0	4.2	541	2.04	12.2	977.5	6.5	142	0.2	2.7	0.2	6	1.93
1456506	Rock	1.54	1.210	15.8	21.2	7.7	28	0.6	1.6	4.5	799	2.39	13.8	1296.1	6.8	117	0.1	1.9	0.1	12	1.69
1456507	Rock	1.91	1.384	95.8	13.0	9.8	26	0.9	3.7	4.8	938	2.41	11.9	1075.3	6.8	144	0.4	1.6	0.5	9	2.27



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456533 Rock	0.032	31	10	0.23	1098	0.015	<20	0.62	0.048	0.28	0.3	0.19	5.0	0.2	<0.05	3	<0.5	<0.2	
1456534 Rock	0.014	11	7	0.07	1662	0.001	<20	0.38	0.046	0.19	0.1	0.28	3.7	<0.1	0.06	1	<0.5	<0.2	
1456535 Rock	0.015	13	6	0.06	1407	0.002	<20	0.43	0.049	0.22	0.3	0.21	4.5	<0.1	<0.05	2	<0.5	<0.2	
1456536 Rock	0.025	19	12	0.08	1429	0.004	<20	0.39	0.037	0.23	0.2	0.16	6.6	<0.1	<0.05	2	<0.5	<0.2	
1456537 Rock	0.012	20	5	0.04	1644	0.001	<20	0.33	0.048	0.17	0.3	0.13	3.3	<0.1	<0.05	1	<0.5	<0.2	
1456538 Rock	0.035	16	4	0.06	834	0.002	<20	0.40	0.026	0.20	0.3	0.33	5.7	0.2	<0.05	2	<0.5	<0.2	
1456539 Rock	0.036	12	4	0.07	4197	0.001	<20	0.56	0.014	0.26	0.4	0.27	6.3	0.1	0.10	2	<0.5	<0.2	
1456540 Rock Pulp	0.068	12	44	0.84	259	0.089	<20	1.47	0.079	0.19	8.1	0.68	4.7	1.3	1.47	6	3.5	0.6	
1456541 Rock	0.027	15	5	0.06	1392	0.002	<20	0.42	0.020	0.23	0.3	0.15	4.9	<0.1	<0.05	2	<0.5	<0.2	
1456542 Rock	0.021	25	4	0.05	861	0.002	<20	0.32	0.027	0.20	0.3	0.09	2.7	<0.1	<0.05	1	<0.5	<0.2	
1456543 Rock	0.049	22	5	0.06	1505	0.002	<20	0.41	0.042	0.23	0.5	0.07	4.2	<0.1	<0.05	1	<0.5	<0.2	
1456544 Rock	0.068	12	3	0.09	1291	0.003	<20	0.51	0.023	0.25	0.1	0.10	5.3	0.1	<0.05	2	<0.5	<0.2	
1456545 Rock	0.076	11	4	0.10	1281	0.002	<20	0.64	0.014	0.29	0.1	0.09	4.8	0.1	<0.05	2	<0.5	<0.2	
1456546 Rock	0.045	20	6	0.06	781	0.002	<20	0.37	0.030	0.21	0.2	0.07	4.1	<0.1	<0.05	1	<0.5	<0.2	
1456547 Rock	0.049	26	10	0.13	424	0.011	<20	0.46	0.037	0.27	0.1	0.06	5.0	0.1	<0.05	2	<0.5	<0.2	
1456548 Rock	0.040	20	4	0.07	569	0.006	<20	0.43	0.035	0.25	0.1	0.08	4.4	<0.1	<0.05	2	<0.5	<0.2	
1419684 Rock	0.054	41	6	0.24	268	0.052	<20	0.84	0.023	0.51	0.6	0.07	7.4	0.2	<0.05	4	<0.5	<0.2	
1419685 Rock	0.038	36	10	0.19	983	0.043	<20	0.64	0.042	0.36	0.5	0.11	4.0	0.1	<0.05	4	<0.5	0.2	
1419686 Rock	0.040	12	5	0.08	719	0.002	<20	0.50	0.006	0.23	0.5	0.24	7.6	0.1	<0.05	2	<0.5	0.2	
1419687 Rock	0.047	19	4	0.08	580	0.006	<20	0.54	0.025	0.29	0.4	0.34	7.9	0.1	<0.05	3	<0.5	0.2	
1419688 Rock	0.039	26	4	0.11	468	0.011	<20	0.57	0.029	0.31	0.7	0.10	6.0	0.1	<0.05	3	<0.5	<0.2	
1419689 Rock	0.048	41	4	0.32	553	0.078	<20	0.90	0.046	0.63	0.5	0.10	5.1	0.3	<0.05	5	<0.5	<0.2	
1419690 Rock	0.048	41	5	0.31	587	0.075	<20	0.87	0.042	0.61	0.6	0.11	5.1	0.3	<0.05	5	<0.5	0.2	
1419691 Rock	0.088	42	7	0.30	862	0.060	<20	0.92	0.027	0.60	0.4	0.10	6.2	0.3	<0.05	5	<0.5	0.4	
1419692 Rock	0.090	32	9	0.35	880	0.074	<20	1.01	0.031	0.67	0.4	0.16	7.8	0.3	<0.05	4	<0.5	0.2	
1419693 Rock	0.065	40	5	0.16	982	0.040	<20	0.72	0.046	0.41	0.4	0.51	9.9	0.2	<0.05	4	<0.5	0.3	
1456504 Rock	0.049	13	10	0.28	1592	<0.001	<20	0.32	0.005	0.25	0.8	0.59	4.4	<0.1	0.22	<1	<0.5	0.2	
1456505 Rock	0.042	13	13	0.30	850	<0.001	<20	0.32	0.005	0.24	0.6	0.57	4.2	<0.1	0.37	1	<0.5	0.4	
1456506 Rock	0.058	20	4	0.49	718	0.002	<20	0.33	0.023	0.25	0.3	0.60	5.5	<0.1	0.54	1	<0.5	0.6	
1456507 Rock	0.042	16	6	0.73	936	<0.001	<20	0.29	0.006	0.24	0.4	0.73	6.6	<0.1	0.52	<1	<0.5	1.1	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 3 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456508	Rock	1.55	1.725	85.9	22.4	13.0	24	1.1	3.7	5.4	1379	2.49	30.4	3162.9	7.4	169	0.2	2.8	0.6	12	1.78
1419734	Rock	2.24	0.156	4.1	16.4	5.2	40	<0.1	7.4	4.9	680	2.07	11.1	97.6	3.5	127	<0.1	1.0	0.1	13	2.09
1419735	Rock	1.95	0.149	3.9	10.3	7.4	29	0.4	2.3	4.2	557	2.19	7.0	139.0	12.2	85	<0.1	0.7	0.4	6	1.47
1419736	Rock	2.09	0.185	2.2	5.1	5.6	21	0.2	2.0	3.0	457	1.69	6.7	153.3	10.3	85	<0.1	0.5	0.3	6	1.41
1419737	Rock	2.57	0.138	3.7	4.6	7.5	18	0.3	2.1	3.0	432	1.75	12.2	75.4	10.4	72	<0.1	0.3	0.3	3	1.24
1419738	Rock	2.12	0.016	7.1	6.0	7.1	25	<0.1	2.1	4.4	480	2.31	20.8	12.1	5.6	74	<0.1	0.6	0.4	4	0.78
1419739	Rock	1.51	0.023	8.2	7.0	5.6	18	0.1	2.0	3.3	430	1.85	6.0	20.4	10.0	101	<0.1	0.6	0.2	3	1.19
1419740	Rock Pulp	0.12	2.186	55.6	2144.2	1241.0	3549	26.4	179.9	19.6	598	4.81	1140.2	1161.7	2.4	73	21.6	16.8	9.7	52	1.39
1419741	Rock	1.80	<0.005	2.5	5.8	4.6	29	<0.1	3.0	4.2	392	1.84	3.0	<0.5	14.4	113	<0.1	0.7	0.1	8	1.23
1419742	Rock	2.47	0.006	7.4	15.7	5.4	23	<0.1	2.1	3.6	315	2.12	7.7	<0.5	9.6	115	<0.1	1.6	0.4	4	1.08
1419743	Rock	2.43	0.033	2.7	8.1	9.3	16	0.2	2.7	2.6	336	1.46	15.0	24.0	12.5	114	<0.1	1.3	0.1	4	1.34
1419704	Rock	1.46	<0.005	1.5	17.1	6.4	46	<0.1	1.7	3.2	486	2.15	5.3	<0.5	16.5	38	0.2	1.3	0.1	7	0.79
1419705	Rock	2.02	<0.005	1.6	12.3	5.0	37	<0.1	1.9	3.7	447	2.00	21.5	0.5	15.5	24	<0.1	0.8	0.3	9	0.36
1419706	Rock	1.56	<0.005	1.7	12.1	5.6	50	<0.1	2.2	3.5	480	2.27	6.9	5.4	18.1	25	<0.1	0.3	0.3	9	0.23
1419707	Rock	1.41	<0.005	2.0	6.4	4.9	40	<0.1	2.3	2.5	340	1.61	5.1	<0.5	19.0	32	<0.1	0.4	0.2	7	0.27
1419708	Rock	2.13	<0.005	1.6	9.4	5.8	45	<0.1	1.9	3.5	493	1.98	6.5	<0.5	15.5	46	<0.1	0.6	0.1	9	0.65
1419709	Rock	1.83	0.007	3.6	13.0	16.5	31	<0.1	3.9	3.6	927	2.36	41.2	1.1	7.3	105	0.2	1.4	0.4	8	3.76
1419710	Rock Pulp	0.12	0.775	4.1	33.4	5.6	50	0.4	23.2	9.3	393	2.46	6.7	538.2	0.9	40	0.2	0.8	0.1	58	0.79
1419711	Rock	1.50	0.911	3.3	8.8	9.0	24	0.3	1.7	2.4	497	1.90	11.5	1336.5	10.9	51	<0.1	0.8	0.3	7	1.75
1419712	Rock	1.50	0.929	2.4	21.6	5.3	25	0.6	1.3	2.8	300	1.97	8.6	2115.4	10.5	44	<0.1	1.3	0.3	5	0.47
1419713	Rock	0.68	1.142	2.7	17.9	5.2	30	0.4	1.7	3.2	309	2.12	3.4	868.1	16.0	35	<0.1	0.8	0.5	8	0.26
1419694	Rock	2.41	<0.005	1.4	17.7	10.3	30	<0.1	1.5	1.3	191	1.20	8.5	2.4	17.6	10	0.1	0.9	0.4	<2	0.04
1419695	Rock	1.64	0.005	1.7	10.2	7.1	31	<0.1	1.9	0.8	307	1.12	10.4	<0.5	20.7	8	0.1	0.7	0.2	2	0.03
1419696	Rock	2.08	<0.005	1.3	11.9	6.1	26	<0.1	1.4	0.8	142	0.97	4.5	<0.5	19.5	10	<0.1	0.7	0.1	<2	0.03
1419697	Rock	1.51	<0.005	1.6	11.6	11.2	27	<0.1	1.4	1.1	146	1.03	18.7	1.7	21.3	9	<0.1	1.2	0.3	2	0.04
1419698	Rock	1.87	<0.005	2.1	10.4	19.6	41	0.1	1.8	2.8	459	2.12	20.2	1.0	18.0	15	0.1	1.0	0.3	3	0.12
1419699	Rock	1.87	<0.005	1.8	15.1	6.1	49	<0.1	1.2	2.9	454	2.20	6.7	<0.5	18.1	14	<0.1	0.4	0.3	4	0.13
1419700	Rock Pulp	0.12	2.015	66.8	2262.9	1300.3	3838	26.1	187.0	20.8	647	5.34	1215.2	892.3	3.0	84	24.9	19.0	11.1	56	1.46
1419701	Rock	1.65	<0.005	2.2	33.9	6.5	54	<0.1	1.5	3.4	605	2.59	8.9	<0.5	16.8	24	0.1	1.0	0.5	4	0.15
1419702	Rock	1.97	<0.005	2.2	11.2	7.2	35	<0.1	1.4	3.0	451	2.10	4.4	<0.5	13.8	64	<0.1	0.9	0.1	9	0.76



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1456508	Rock	0.060	17	17	0.54	1060	<0.001	<20	0.38	0.013	0.26	0.8	0.78	5.6	0.2	0.49	1	<0.5	1.2	
1419734	Rock	0.030	9	15	0.39	1143	0.002	<20	0.25	0.015	0.19	3.5	0.34	4.3	<0.1	0.13	1	<0.5	<0.2	
1419735	Rock	0.041	22	10	0.27	691	0.003	<20	0.33	0.042	0.22	2.6	0.11	3.5	<0.1	0.53	1	<0.5	0.3	
1419736	Rock	0.027	15	10	0.26	502	0.001	<20	0.26	0.035	0.18	3.0	0.15	3.0	<0.1	0.38	1	<0.5	<0.2	
1419737	Rock	0.022	16	8	0.05	644	<0.001	<20	0.30	0.029	0.18	1.2	0.13	3.2	<0.1	0.28	<1	<0.5	0.3	
1419738	Rock	0.037	10	6	0.07	477	<0.001	<20	0.36	0.013	0.23	0.7	0.15	3.7	<0.1	0.29	1	<0.5	<0.2	
1419739	Rock	0.026	16	8	0.09	922	<0.001	<20	0.29	0.029	0.21	1.2	0.13	2.5	<0.1	0.36	1	<0.5	<0.2	
1419740	Rock Pulp	0.068	11	42	0.81	201	0.081	<20	1.37	0.072	0.18	8.1	0.69	4.5	1.2	1.46	6	3.3	0.5	
1419741	Rock	0.043	27	11	0.18	612	0.003	<20	0.29	0.037	0.20	1.5	0.14	3.4	<0.1	0.14	1	<0.5	<0.2	
1419742	Rock	0.027	15	10	0.17	534	0.001	<20	0.25	0.037	0.17	3.7	0.20	4.2	<0.1	0.63	1	0.7	<0.2	
1419743	Rock	0.019	14	11	0.30	888	<0.001	<20	0.23	0.034	0.15	2.1	0.29	2.8	<0.1	0.25	<1	<0.5	<0.2	
1419704	Rock	0.032	42	7	0.19	208	0.040	<20	0.56	0.040	0.38	1.0	0.11	4.1	0.2	<0.05	4	<0.5	<0.2	
1419705	Rock	0.039	40	8	0.25	175	0.041	<20	0.60	0.047	0.37	0.7	0.10	3.3	0.2	<0.05	4	<0.5	<0.2	
1419706	Rock	0.046	46	8	0.30	221	0.099	<20	0.88	0.045	0.64	0.8	0.03	3.4	0.4	<0.05	6	<0.5	<0.2	
1419707	Rock	0.024	44	9	0.20	271	0.056	<20	0.57	0.052	0.36	1.1	0.04	2.5	0.2	<0.05	4	<0.5	<0.2	
1419708	Rock	0.039	41	7	0.26	390	0.058	<20	0.63	0.046	0.45	0.7	0.08	3.3	0.3	<0.05	5	<0.5	<0.2	
1419709	Rock	0.018	14	9	0.07	1920	<0.001	<20	0.29	0.005	0.15	0.8	0.23	4.3	<0.1	<0.05	<1	<0.5	<0.2	
1419710	Rock Pulp	0.063	5	31	0.72	101	0.121	<20	1.46	0.078	0.13	9.8	0.04	5.0	<0.1	<0.05	5	<0.5	<0.2	
1419711	Rock	0.017	22	6	0.04	723	<0.001	<20	0.28	0.015	0.17	0.5	0.25	3.6	<0.1	<0.05	1	<0.5	<0.2	
1419712	Rock	0.023	22	6	0.04	591	0.003	<20	0.32	0.027	0.20	0.3	0.17	3.6	<0.1	<0.05	1	<0.5	<0.2	
1419713	Rock	0.034	36	8	0.09	505	0.019	<20	0.40	0.042	0.26	1.0	0.18	3.8	<0.1	<0.05	3	<0.5	0.3	
1419694	Rock	0.005	24	5	0.02	164	0.003	<20	0.22	0.040	0.12	1.2	0.15	2.0	<0.1	<0.05	1	<0.5	<0.2	
1419695	Rock	0.003	26	6	0.03	153	0.003	<20	0.24	0.048	0.15	1.1	0.12	1.4	<0.1	<0.05	2	<0.5	<0.2	
1419696	Rock	0.003	25	6	0.06	201	0.010	<20	0.26	0.049	0.18	1.9	0.14	1.2	<0.1	<0.05	2	<0.5	<0.2	
1419697	Rock	0.005	30	6	0.06	96	0.005	<20	0.27	0.038	0.17	1.3	0.07	1.3	<0.1	<0.05	2	<0.5	<0.2	
1419698	Rock	0.028	43	10	0.25	212	0.049	<20	0.73	0.037	0.48	0.7	0.09	2.7	0.2	<0.05	5	<0.5	<0.2	
1419699	Rock	0.036	46	4	0.24	204	0.072	<20	0.75	0.034	0.52	0.6	0.07	2.8	0.3	<0.05	5	<0.5	<0.2	
1419700	Rock Pulp	0.074	13	45	0.87	272	0.091	<20	1.46	0.078	0.19	8.6	0.77	4.9	1.3	1.50	6	3.8	0.5	
1419701	Rock	0.046	48	6	0.18	419	0.050	<20	0.67	0.044	0.45	0.6	0.23	4.8	0.2	<0.05	5	<0.5	<0.2	
1419702	Rock	0.029	34	7	0.06	1640	0.016	<20	0.34	0.049	0.21	0.8	0.10	4.7	<0.1	<0.05	2	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419703	Rock	1.90	<0.005	2.1	14.6	8.0	36	<0.1	2.0	3.0	542	2.04	6.7	<0.5	15.8	56	0.1	2.3	0.1	5	1.50
1419744	Rock	3.08	0.008	2.5	5.7	5.3	11	<0.1	1.8	2.2	218	1.25	10.9	4.3	11.4	72	<0.1	0.6	0.2	<2	0.73
1419745	Rock	2.22	0.188	21.4	6.1	5.8	8	0.2	1.7	2.3	268	1.08	8.3	223.2	12.3	118	<0.1	0.8	0.3	<2	0.95
1419746	Rock	2.46	1.932	958.4	19.8	73.8	19	3.1	5.4	6.9	510	1.86	7.3	2580.2	4.2	167	2.1	5.7	8.7	4	1.53
1419747	Rock	2.56	1.205	45.6	6.4	8.2	19	0.5	2.1	5.5	654	2.35	7.6	950.4	8.4	163	0.2	0.8	0.6	8	2.37
1419748	Rock	1.51	0.473	19.6	6.9	5.1	11	0.3	2.1	4.7	377	1.88	5.7	600.8	13.1	144	0.1	0.8	0.2	4	1.52
1419749	Rock	2.34	1.868	111.9	11.6	15.3	18	1.1	3.8	6.6	594	2.28	13.2	1143.9	6.8	147	0.3	1.7	1.3	6	1.80
1419750	Rock	0.42	0.015	1.7	1.5	1.8	14	<0.1	2.1	0.8	229	0.49	<0.5	68.4	0.2	57	<0.1	<0.1	<0.1	<2	18.43
1456501	Rock	2.02	0.297	7.1	8.7	5.2	28	0.2	1.8	5.2	508	2.36	4.9	195.6	8.2	105	<0.1	1.0	0.2	8	1.37
1456502	Rock	1.79	1.431	46.9	15.0	16.2	30	0.6	3.8	4.6	511	2.26	12.8	803.8	5.8	119	0.2	2.9	0.4	7	1.67
1456503	Rock	1.04	0.762	18.3	50.5	8.8	28	0.5	2.6	5.1	685	2.41	17.5	577.6	6.4	159	0.1	11.0	0.2	8	2.08
1456521	Rock	1.74	0.009	2.0	19.2	9.0	33	<0.1	23.7	9.1	622	2.48	12.7	1.9	13.6	78	<0.1	0.9	0.3	25	2.77
1456522	Rock	1.54	<0.005	1.6	6.1	10.5	27	<0.1	3.2	3.1	372	1.84	4.2	<0.5	8.0	67	<0.1	0.7	0.2	8	0.71
1456523	Rock	1.33	<0.005	1.9	4.7	11.0	26	<0.1	3.4	3.0	361	1.79	2.2	1.3	9.0	55	<0.1	0.3	0.2	11	0.50
1456524	Rock	1.99	<0.005	1.6	12.7	5.7	19	<0.1	10.2	6.4	350	1.64	1.9	1.3	15.9	39	<0.1	0.8	<0.1	15	1.48
1456525	Rock	2.70	<0.005	1.8	5.4	8.9	27	<0.1	3.7	1.7	241	1.25	1.1	<0.5	19.5	19	<0.1	0.6	0.2	3	0.10
1456526	Rock	2.31	0.022	2.0	13.8	6.0	35	<0.1	2.2	4.4	458	2.52	1.3	5.0	13.8	28	<0.1	0.4	0.7	17	0.24
1456527	Rock	2.20	<0.005	2.3	7.2	5.7	33	<0.1	2.1	4.2	533	2.24	1.0	1.0	11.4	48	<0.1	0.3	0.4	11	1.18
1456528	Rock	1.93	0.021	5.2	10.5	10.7	30	<0.1	2.0	4.0	515	2.01	2.9	16.7	9.2	69	<0.1	1.1	0.4	10	1.96
1456529	Rock	1.31	0.087	4.0	12.3	8.8	35	<0.1	2.8	4.3	540	2.46	3.3	40.7	9.0	60	<0.1	1.0	0.2	9	1.14
1456530	Rock	1.07	0.044	2.9	6.4	9.2	37	<0.1	1.6	4.1	752	2.33	2.9	14.5	7.9	87	<0.1	0.3	<0.1	11	2.57
1456531	Rock	1.72	0.278	2.6	6.5	8.3	35	<0.1	2.8	3.6	711	2.17	2.8	18.6	8.3	78	0.1	0.4	<0.1	13	2.68
1456532	Rock	1.26	<0.005	3.3	16.4	12.3	33	<0.1	3.2	4.1	692	2.10	4.4	<0.5	10.9	78	<0.1	1.8	0.1	5	1.52
1419681	Rock	1.29	0.125	6.6	4.1	6.6	12	0.1	2.9	2.0	520	1.61	22.6	186.0	15.6	113	0.1	0.9	<0.1	7	1.19
1419682	Rock	1.31	0.255	11.4	6.0	5.4	13	0.1	3.5	1.8	378	1.59	7.6	211.8	18.8	75	<0.1	1.0	<0.1	7	0.91
1419683	Rock	1.92	0.334	13.9	6.6	7.2	14	0.2	3.6	2.4	466	1.68	14.7	153.0	19.4	113	0.1	1.3	0.1	7	1.03
1456519	Rock	1.06	0.038	3.4	14.7	12.3	30	<0.1	4.5	4.0	761	1.92	3.6	9.1	13.7	84	0.1	1.6	0.2	6	1.67
1456520	Rock	0.66	<0.005	0.1	3.2	1.5	13	<0.1	1.1	0.6	242	0.45	<0.5	1.9	<0.1	44	<0.1	<0.1	<0.1	<2	21.20
1419724	Rock	1.55	0.084	2.5	10.0	8.6	17	0.4	3.0	1.8	402	1.52	5.4	50.8	7.9	181	<0.1	0.9	0.3	3	1.02
1419725	Rock	1.63	0.012	3.1	13.7	5.9	18	<0.1	2.1	2.3	318	1.65	4.3	11.1	10.6	154	<0.1	0.9	0.3	5	0.91



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Ti ppm	S %	Ga ppm	Se ppm	Te ppm	
1419703	Rock	0.018	36	7	0.05	552	0.003	<20	0.32	0.041	0.18	0.6	0.34	3.8	<0.1	<0.05	2	<0.5	<0.2
1419744	Rock	0.008	17	9	0.12	464	<0.001	<20	0.29	0.020	0.23	1.5	0.15	1.9	<0.1	0.37	1	<0.5	<0.2
1419745	Rock	0.012	17	8	0.21	1206	<0.001	<20	0.35	0.004	0.30	1.3	0.50	2.1	<0.1	0.38	<1	<0.5	0.3
1419746	Rock	0.040	9	8	0.29	421	<0.001	<20	0.28	0.002	0.18	2.5	1.63	4.5	0.6	0.69	<1	0.7	6.2
1419747	Rock	0.057	15	6	0.26	1205	<0.001	<20	0.36	0.002	0.29	0.7	0.99	5.8	0.1	0.44	1	<0.5	0.6
1419748	Rock	0.038	14	7	0.10	1191	<0.001	<20	0.29	0.002	0.24	0.9	0.65	3.9	<0.1	0.41	<1	<0.5	0.4
1419749	Rock	0.037	10	9	0.51	535	<0.001	<20	0.33	0.006	0.24	1.6	0.95	4.7	<0.1	0.86	<1	<0.5	1.5
1419750	Rock	0.021	<1	<1	12.05	80	<0.001	<20	0.04	<0.001	0.02	0.2	0.02	0.5	<0.1	<0.05	<1	<0.5	<0.2
1456501	Rock	0.041	14	9	0.27	732	0.004	<20	0.32	0.018	0.25	1.7	0.48	3.3	<0.1	0.36	1	<0.5	0.2
1456502	Rock	0.024	7	8	0.30	739	<0.001	<20	0.23	0.005	0.17	1.6	0.76	3.3	<0.1	0.49	<1	<0.5	0.6
1456503	Rock	0.058	9	8	0.46	957	<0.001	<20	0.26	<0.001	0.23	1.0	0.45	3.6	<0.1	0.36	<1	<0.5	0.4
1456521	Rock	0.050	27	15	0.30	1157	0.009	<20	0.56	0.025	0.24	0.3	0.21	6.4	0.1	<0.05	2	<0.5	<0.2
1456522	Rock	0.014	11	3	0.09	1935	0.001	<20	0.31	0.025	0.13	0.2	0.44	3.8	<0.1	<0.05	<1	<0.5	<0.2
1456523	Rock	0.010	14	6	0.07	2410	0.002	<20	0.32	0.027	0.13	0.2	0.23	3.7	<0.1	0.05	<1	<0.5	<0.2
1456524	Rock	0.009	21	11	0.09	658	0.002	<20	0.31	0.027	0.18	0.4	0.26	5.1	<0.1	<0.05	<1	<0.5	<0.2
1456525	Rock	0.011	28	7	0.05	202	0.005	<20	0.29	0.035	0.17	0.6	0.16	1.9	<0.1	<0.05	1	<0.5	<0.2
1456526	Rock	0.044	24	5	0.16	573	0.023	<20	0.50	0.028	0.33	0.4	0.17	5.3	0.2	<0.05	3	<0.5	<0.2
1456527	Rock	0.031	20	5	0.10	332	0.007	<20	0.36	0.027	0.22	0.4	0.15	6.0	0.1	<0.05	2	<0.5	<0.2
1456528	Rock	0.015	14	4	0.05	922	0.002	<20	0.28	0.018	0.16	0.5	0.19	4.2	<0.1	<0.05	1	<0.5	<0.2
1456529	Rock	0.034	15	6	0.05	361	0.002	<20	0.35	0.020	0.19	0.3	0.13	3.3	<0.1	<0.05	1	<0.5	<0.2
1456530	Rock	0.040	15	5	0.06	1487	0.002	<20	0.28	0.019	0.16	0.4	0.07	2.9	<0.1	<0.05	<1	<0.5	<0.2
1456531	Rock	0.033	15	5	0.05	1552	0.002	<20	0.28	0.026	0.16	0.4	0.06	3.2	<0.1	<0.05	<1	<0.5	<0.2
1456532	Rock	0.027	15	5	0.05	1109	0.001	<20	0.30	0.014	0.16	0.2	0.11	2.4	<0.1	<0.05	<1	<0.5	<0.2
1419681	Rock	0.009	10	9	0.37	893	<0.001	<20	0.17	0.025	0.12	0.6	0.37	1.8	<0.1	0.28	<1	<0.5	<0.2
1419682	Rock	0.006	23	11	0.26	625	<0.001	<20	0.20	0.008	0.16	0.6	0.43	1.3	<0.1	0.13	<1	<0.5	<0.2
1419683	Rock	0.010	15	12	0.30	1068	<0.001	<20	0.23	0.008	0.15	2.4	0.46	1.7	<0.1	0.20	<1	<0.5	<0.2
1456519	Rock	0.019	16	8	0.06	690	0.001	<20	0.34	0.015	0.20	0.1	0.13	2.7	<0.1	<0.05	1	<0.5	<0.2
1456520	Rock	0.014	<1	<1	11.83	31	<0.001	<20	0.03	<0.001	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1419724	Rock	0.013	14	7	0.03	3562	<0.001	<20	0.20	0.029	0.12	1.0	0.54	1.9	<0.1	0.14	<1	<0.5	0.4
1419725	Rock	0.020	20	10	0.02	3424	<0.001	<20	0.18	0.035	0.12	2.7	0.42	2.2	<0.1	0.14	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419726	Rock	2.37	0.061	2.9	16.7	4.8	13	0.2	1.6	2.9	397	1.55	2.8	62.4	9.2	149	<0.1	0.7	0.3	4	0.95
1419727	Rock	1.80	0.079	4.1	15.9	7.5	25	0.2	1.9	2.1	176	1.60	15.8	43.4	17.1	35	<0.1	1.0	0.9	3	0.24
1419728	Rock	1.85	0.012	2.3	16.3	5.5	24	<0.1	1.2	2.4	253	1.70	2.1	8.9	16.8	30	<0.1	0.8	0.7	4	0.14
1419729	Rock	2.84	0.046	3.0	25.8	6.1	21	0.1	1.9	2.2	105	1.98	4.4	15.4	13.5	35	<0.1	0.8	1.3	5	0.09
1419730	Rock	1.99	0.161	2.8	34.2	6.2	20	0.2	1.8	2.0	125	2.18	5.0	18.2	13.9	38	<0.1	1.0	1.8	6	0.09
1419731	Rock	1.97	0.013	2.7	12.1	11.6	29	<0.1	2.2	3.2	379	2.04	11.6	10.9	13.7	53	<0.1	0.9	1.2	5	0.57
1419732	Rock	2.77	0.040	3.4	17.4	8.4	24	0.2	1.5	3.3	319	2.13	6.1	12.0	10.2	48	<0.1	1.0	2.7	3	0.73
1419733	Rock	2.61	0.062	3.7	13.9	4.6	23	0.1	2.2	2.9	381	1.97	6.9	48.5	13.0	52	<0.1	0.6	0.6	6	0.75
1419714	Rock	1.65	0.028	2.7	17.1	4.7	36	<0.1	1.9	3.1	432	2.27	3.6	3.3	17.1	24	<0.1	0.6	0.6	7	0.16
1419715	Rock	1.88	<0.005	3.1	10.5	7.5	37	<0.1	3.5	3.9	372	2.08	4.1	3.1	17.9	32	<0.1	0.5	0.3	11	0.42
1419716	Rock	1.97	<0.005	2.3	13.9	6.2	32	<0.1	1.3	2.3	288	1.95	5.6	0.9	14.5	47	<0.1	1.8	0.4	3	0.74
1419717	Rock	1.34	<0.005	2.4	6.9	10.9	26	<0.1	1.6	2.1	347	1.75	6.2	4.3	11.1	32	<0.1	0.7	0.4	<2	0.34
1419718	Rock	2.06	0.009	2.3	15.8	20.7	22	0.1	0.6	2.3	442	1.85	11.3	6.0	7.4	49	<0.1	1.9	0.6	2	2.08
1419719	Rock	1.54	0.012	1.9	18.1	12.9	26	0.1	1.5	3.7	532	2.37	7.9	18.1	11.0	350	0.1	1.2	0.7	8	2.47
1419720	Rock	0.51	0.010	0.2	1.6	1.6	12	<0.1	1.3	1.1	231	0.45	<0.5	<0.5	0.2	49	<0.1	<0.1	<0.1	<2	20.89
1419721	Rock	1.13	0.009	2.0	9.7	14.2	19	<0.1	1.4	2.3	541	1.36	4.7	4.4	6.2	151	<0.1	1.3	0.1	4	2.12
1419722	Rock	1.80	0.034	3.6	25.2	5.0	24	0.3	1.7	3.5	519	2.06	4.0	70.7	15.9	71	0.1	1.5	0.5	5	1.79
1419723	Rock	2.33	0.011	3.4	8.8	7.5	23	<0.1	1.1	2.4	407	1.77	2.6	10.6	17.5	224	<0.1	0.6	0.3	4	1.38
1456509	Rock	3.40	0.077	3.2	11.9	9.9	28	<0.1	13.2	6.2	502	2.12	16.5	27.6	13.0	58	<0.1	0.8	0.4	15	1.27
1456510	Rock Pulp	0.12	0.815	4.2	33.8	5.4	51	0.3	23.8	9.6	401	2.54	6.5	726.3	0.9	39	0.2	0.8	0.1	57	0.79
1456511	Rock	2.13	0.030	2.3	5.6	8.5	29	<0.1	2.9	3.3	364	1.92	3.5	43.9	9.9	58	<0.1	0.4	0.3	9	0.36
1456512	Rock	0.56	0.036	3.1	7.1	5.0	29	<0.1	6.4	3.1	331	1.82	1.8	40.3	10.3	46	<0.1	0.4	<0.1	8	0.66
1456513	Rock	2.52	0.037	3.1	31.9	9.7	34	<0.1	42.3	19.2	706	2.92	1.5	32.5	8.1	88	<0.1	1.2	0.2	44	4.77
1456514	Rock	3.35	0.025	2.5	7.3	8.6	24	<0.1	2.8	2.3	286	1.33	2.6	24.1	16.7	33	<0.1	0.6	0.3	3	0.25
1456515	Rock	3.35	0.078	3.6	16.8	9.7	44	<0.1	4.2	6.3	630	2.97	2.9	35.9	12.1	64	<0.1	0.5	0.9	17	1.11
1456516	Rock	3.21	0.497	2.1	12.6	9.3	31	0.1	2.1	4.7	485	2.22	1.4	518.5	11.9	69	<0.1	0.3	0.5	14	2.11
1456517	Rock	2.79	0.186	3.5	9.2	10.7	30	<0.1	2.2	3.5	555	2.04	2.4	168.2	10.5	94	<0.1	0.8	0.2	10	2.15
1456518	Rock	1.68	0.082	2.2	11.3	15.3	28	<0.1	1.9	3.3	554	1.71	3.6	31.6	16.6	93	<0.1	1.2	0.2	6	1.09
1184653	Rock	2.52	0.007	1.6	2.3	2.0	43	<0.1	7.4	7.6	791	2.53	7.3	5.8	10.7	172	<0.1	0.3	0.2	36	1.67
1184654	Rock	3.22	0.007	1.8	2.4	2.3	41	<0.1	7.6	6.9	772	2.37	3.4	1.5	10.0	168	<0.1	0.5	0.2	38	1.51



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
1419726	Rock	0.016	17	9	0.03	2400	<0.001	<20	0.16	0.027	0.09	3.4	0.32	2.3	<0.1	0.22	<1	<0.5	0.2
1419727	Rock	0.019	43	10	0.10	466	0.015	<20	0.30	0.043	0.15	3.3	0.18	2.8	<0.1	0.20	2	<0.5	0.3
1419728	Rock	0.022	36	7	0.08	441	0.013	<20	0.31	0.041	0.19	2.0	0.26	2.6	<0.1	0.18	2	<0.5	<0.2
1419729	Rock	0.021	17	10	0.07	351	0.009	<20	0.27	0.042	0.17	1.7	0.26	2.4	<0.1	0.16	2	<0.5	0.3
1419730	Rock	0.019	22	9	0.07	387	0.010	<20	0.30	0.051	0.20	1.6	0.25	2.2	<0.1	0.22	2	0.5	0.6
1419731	Rock	0.022	23	8	0.03	417	0.002	<20	0.28	0.038	0.15	1.2	0.24	3.2	<0.1	0.22	1	<0.5	<0.2
1419732	Rock	0.017	17	7	0.06	204	0.001	<20	0.34	0.022	0.20	0.9	0.20	2.1	<0.1	0.24	1	0.6	0.5
1419733	Rock	0.029	25	9	0.11	711	0.005	<20	0.28	0.037	0.17	2.3	0.15	2.2	<0.1	0.39	1	0.5	<0.2
1419714	Rock	0.040	38	7	0.14	332	0.037	<20	0.54	0.036	0.33	0.9	0.15	3.4	0.2	<0.05	3	<0.5	<0.2
1419715	Rock	0.037	42	15	0.27	220	0.057	<20	0.67	0.041	0.41	1.2	0.08	3.1	0.3	<0.05	4	<0.5	<0.2
1419716	Rock	0.019	28	7	0.05	255	0.003	<20	0.29	0.034	0.15	0.8	0.16	3.6	<0.1	<0.05	2	<0.5	<0.2
1419717	Rock	0.007	19	6	0.03	207	<0.001	<20	0.26	0.030	0.12	0.6	0.18	2.4	<0.1	<0.05	<1	<0.5	<0.2
1419718	Rock	0.007	11	4	0.05	250	<0.001	<20	0.28	0.002	0.17	0.3	0.18	3.3	<0.1	<0.05	<1	<0.5	<0.2
1419719	Rock	0.031	18	6	0.04	2990	<0.001	<20	0.23	0.031	0.13	0.6	0.24	3.7	<0.1	0.10	<1	<0.5	0.3
1419720	Rock	0.016	<1	<1	11.84	44	<0.001	<20	0.02	<0.001	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1419721	Rock	0.022	10	7	0.08	2729	<0.001	<20	0.17	0.025	0.08	1.9	0.19	2.0	<0.1	0.13	<1	<0.5	<0.2
1419722	Rock	0.033	34	11	0.11	549	0.004	<20	0.26	0.042	0.18	1.6	0.42	2.7	<0.1	0.09	1	<0.5	0.3
1419723	Rock	0.025	36	7	0.06	2864	0.005	<20	0.27	0.033	0.18	1.1	0.35	2.1	<0.1	0.10	1	<0.5	<0.2
1456509	Rock	0.034	24	9	0.13	957	0.003	<20	0.45	0.020	0.19	0.2	0.31	5.0	0.1	<0.05	2	<0.5	<0.2
1456510	Rock Pulp	0.064	4	32	0.73	103	0.123	<20	1.55	0.088	0.14	10.9	0.05	4.7	<0.1	<0.05	5	<0.5	<0.2
1456511	Rock	0.016	16	4	0.07	1408	0.002	<20	0.38	0.024	0.15	0.2	0.25	4.1	<0.1	<0.05	1	<0.5	<0.2
1456512	Rock	0.009	15	7	0.06	752	0.003	<20	0.32	0.028	0.16	0.4	0.17	4.4	<0.1	<0.05	1	<0.5	<0.2
1456513	Rock	0.033	13	50	0.64	1778	0.026	<20	0.90	0.015	0.61	0.1	0.14	10.6	0.3	<0.05	2	<0.5	<0.2
1456514	Rock	0.008	22	5	0.04	290	0.002	<20	0.27	0.026	0.15	0.6	0.10	2.5	<0.1	<0.05	1	<0.5	<0.2
1456515	Rock	0.055	26	6	0.11	541	0.008	<20	0.45	0.026	0.26	0.4	0.27	7.3	0.1	<0.05	2	<0.5	0.4
1456516	Rock	0.038	23	3	0.05	1335	0.003	<20	0.26	0.030	0.15	0.4	0.13	4.8	<0.1	<0.05	1	<0.5	<0.2
1456517	Rock	0.033	17	5	0.06	821	0.001	<20	0.31	0.017	0.18	0.3	0.11	3.3	<0.1	<0.05	1	<0.5	<0.2
1456518	Rock	0.015	18	4	0.06	748	0.001	<20	0.32	0.013	0.18	0.2	0.14	2.5	<0.1	<0.05	1	<0.5	<0.2
1184653	Rock	0.051	24	23	0.87	886	0.092	<20	0.94	0.038	0.77	1.4	0.05	7.7	0.2	0.21	5	<0.5	<0.2
1184654	Rock	0.059	24	24	0.82	1025	0.103	<20	1.01	0.046	0.74	1.5	0.05	6.5	0.2	0.13	6	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1184655	Rock	2.29	0.010	1.5	2.5	8.6	31	<0.1	6.6	6.1	771	1.96	8.9	5.9	8.9	1253	0.1	0.8	0.2	25	3.87
1184656	Rock	2.40	<0.005	1.6	2.3	3.7	39	<0.1	5.8	6.7	663	2.25	6.5	2.5	9.9	365	<0.1	0.8	0.2	31	1.88
1184657	Rock	2.42	0.006	2.3	5.2	5.1	49	<0.1	6.1	8.6	805	2.97	9.2	3.0	7.2	242	0.1	0.9	0.3	24	1.43
1184658	Rock	2.32	<0.005	1.8	4.2	5.5	49	<0.1	5.6	7.4	719	2.31	30.9	2.1	4.5	228	0.2	0.5	0.3	23	2.09
1184659	Rock	3.12	0.007	1.7	3.6	9.8	40	<0.1	6.5	7.1	709	2.41	100.3	0.9	4.3	235	0.1	0.5	0.2	26	2.19
1184660	Rock	1.73	<0.005	1.6	3.7	10.5	41	<0.1	5.5	6.8	696	2.42	96.6	2.7	4.3	245	0.1	0.7	0.2	26	2.33
1184661	Rock	2.51	<0.005	1.7	5.4	5.3	38	<0.1	5.9	6.9	557	2.27	7.9	1.7	8.5	425	<0.1	1.1	<0.1	29	1.71
1184662	Rock	2.59	<0.005	2.2	2.7	2.4	38	<0.1	7.1	7.3	624	2.29	5.6	2.1	10.5	90	<0.1	0.2	0.1	38	1.54
1184623	Rock	0.37	<0.005	0.8	10.3	3.5	37	<0.1	10.7	7.5	488	1.99	20.2	2.9	6.0	94	<0.1	0.6	0.1	31	0.73
1184624	Rock	1.25	0.007	1.1	20.4	5.2	41	<0.1	17.9	7.7	305	2.01	20.8	3.6	3.5	146	0.2	1.2	0.2	32	1.03
1184625	Rock	1.10	0.005	1.1	17.9	5.5	40	<0.1	17.5	8.2	242	1.93	30.5	2.4	3.4	80	0.1	1.3	0.2	32	0.68
1184626	Rock	0.91	<0.005	1.5	29.6	6.6	55	<0.1	24.3	9.6	366	2.16	20.3	3.9	2.8	82	0.2	1.2	0.2	40	1.37
1184627	Rock	1.48	<0.005	1.3	23.6	6.5	52	<0.1	22.7	10.3	513	2.43	28.6	1.4	6.0	92	0.1	1.2	0.1	48	1.48
1184628	Rock	3.61	<0.005	1.3	12.5	5.6	19	<0.1	7.3	4.1	326	1.19	30.5	<0.5	4.6	40	<0.1	1.0	0.1	11	0.27
1184629	Rock	2.23	<0.005	1.4	5.6	6.6	20	<0.1	2.8	2.9	390	1.45	30.4	<0.5	9.0	27	<0.1	0.5	0.3	4	0.10
1184630	Rock	1.67	<0.005	1.3	4.6	6.4	17	<0.1	2.1	2.8	375	1.38	27.2	<0.5	8.6	25	<0.1	0.5	0.3	4	0.10
1184631	Rock	2.83	<0.005	1.5	4.2	7.6	16	<0.1	2.2	2.2	283	1.24	44.0	<0.5	6.0	80	<0.1	0.4	0.3	3	0.09
1184632	Rock	2.52	<0.005	1.5	5.4	8.8	23	<0.1	1.4	2.0	197	1.44	29.8	<0.5	7.6	30	<0.1	0.4	0.4	2	0.19



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 28, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000356.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1184655	Rock	0.048	21	18	0.55	2518	0.056	<20	0.64	0.037	0.46	1.3	0.17	5.3	0.2	0.16	3	<0.5	<0.2
1184656	Rock	0.051	19	16	0.74	1447	0.028	<20	0.54	0.035	0.38	0.7	0.15	8.6	0.1	0.10	3	<0.5	<0.2
1184657	Rock	0.049	9	11	0.60	1345	0.002	<20	0.35	0.030	0.21	0.4	0.25	10.6	0.1	0.16	2	<0.5	<0.2
1184658	Rock	0.007	4	12	0.71	583	<0.001	<20	0.24	0.022	0.12	0.8	0.29	10.4	0.3	0.18	<1	<0.5	<0.2
1184659	Rock	0.006	6	13	0.75	1930	<0.001	<20	0.20	0.025	0.09	1.3	0.51	9.2	0.7	0.18	<1	<0.5	<0.2
1184660	Rock	0.006	6	13	0.75	2154	<0.001	<20	0.19	0.024	0.09	1.5	0.54	9.3	0.7	0.18	<1	<0.5	<0.2
1184661	Rock	0.047	16	18	0.64	1211	0.039	<20	0.51	0.046	0.37	1.0	0.08	7.9	0.2	0.15	3	<0.5	<0.2
1184662	Rock	0.053	24	25	0.78	594	0.095	<20	0.92	0.050	0.70	1.6	0.03	6.5	0.3	0.10	6	<0.5	<0.2
1184623	Rock	0.048	14	21	0.66	579	0.089	<20	0.97	0.023	0.51	0.4	0.16	3.9	0.2	<0.05	4	<0.5	<0.2
1184624	Rock	0.060	11	26	0.52	530	0.052	<20	0.82	0.021	0.22	2.9	0.09	4.0	0.1	0.09	3	1.3	<0.2
1184625	Rock	0.056	10	23	0.40	581	0.039	<20	0.66	0.020	0.17	1.9	0.16	4.0	0.1	<0.05	2	<0.5	<0.2
1184626	Rock	0.073	12	31	0.56	452	0.055	<20	0.93	0.026	0.17	2.4	0.07	4.5	0.1	0.07	3	<0.5	<0.2
1184627	Rock	0.059	17	40	0.75	1402	0.085	<20	0.98	0.051	0.37	1.7	0.10	7.2	0.2	<0.05	4	<0.5	<0.2
1184628	Rock	0.014	9	12	0.14	1261	0.010	<20	0.34	0.019	0.10	4.1	0.24	4.3	0.1	<0.05	<1	<0.5	<0.2
1184629	Rock	0.005	12	5	0.05	575	<0.001	<20	0.25	0.025	0.10	0.9	0.72	7.7	0.2	<0.05	<1	<0.5	<0.2
1184630	Rock	0.004	12	4	0.05	439	<0.001	<20	0.23	0.020	0.09	0.9	0.64	7.3	0.2	<0.05	<1	<0.5	<0.2
1184631	Rock	0.003	9	5	0.03	2526	<0.001	<20	0.22	0.011	0.10	1.6	0.27	5.8	0.2	0.06	<1	<0.5	<0.2
1184632	Rock	0.003	11	4	0.04	464	<0.001	<20	0.24	0.017	0.10	1.0	0.26	7.2	0.1	<0.05	<1	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000356.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1456544	Rock	1.34	0.012	2.8	7.4	9.4	48	<0.1	2.1	5.5	974	3.05	5.0	6.0	5.3	123	0.1	0.3	0.1	16	2.78
REP 1456544	QC			2.8	6.9	9.4	46	<0.1	1.9	5.7	988	3.12	4.9	4.0	5.2	124	0.1	0.3	0.1	16	2.85
1419686	Rock	3.17	0.008	2.7	21.1	12.7	33	<0.1	2.5	4.5	629	2.76	53.8	5.7	5.1	36	0.1	0.7	0.8	6	0.18
REP 1419686	QC		0.006																		
1419708	Rock	2.13	<0.005	1.6	9.4	5.8	45	<0.1	1.9	3.5	493	1.98	6.5	<0.5	15.5	46	<0.1	0.6	0.1	9	0.65
REP 1419708	QC			1.5	9.2	5.8	43	<0.1	1.8	3.5	482	1.94	6.5	<0.5	16.5	48	<0.1	0.6	0.2	9	0.63
1419697	Rock	1.51	<0.005	1.6	11.6	11.2	27	<0.1	1.4	1.1	146	1.03	18.7	1.7	21.3	9	<0.1	1.2	0.3	2	0.04
REP 1419697	QC		<0.005																		
1456528	Rock	1.93	0.021	5.2	10.5	10.7	30	<0.1	2.0	4.0	515	2.01	2.9	16.7	9.2	69	<0.1	1.1	0.4	10	1.96
REP 1456528	QC			5.0	10.3	10.5	30	<0.1	2.1	3.9	505	2.01	2.9	19.5	9.3	72	<0.1	1.0	0.4	10	1.96
1456514	Rock	3.35	0.025	2.5	7.3	8.6	24	<0.1	2.8	2.3	286	1.33	2.6	24.1	16.7	33	<0.1	0.6	0.3	3	0.25
REP 1456514	QC			2.1	7.3	8.7	24	<0.1	3.0	2.2	281	1.29	2.5	9.6	16.7	34	<0.1	0.6	0.3	3	0.25
1184627	Rock	1.48	<0.005	1.3	23.6	6.5	52	<0.1	22.7	10.3	513	2.43	28.6	1.4	6.0	92	0.1	1.2	0.1	48	1.48
REP 1184627	QC		<0.005																		
1184630	Rock	1.67	<0.005	1.3	4.6	6.4	17	<0.1	2.1	2.8	375	1.38	27.2	<0.5	8.6	25	<0.1	0.5	0.3	4	0.10
REP 1184630	QC		<0.005																		
Core Reject Duplicates																					
1456547	Rock	2.17	0.007	2.8	17.4	6.5	32	<0.1	7.9	6.5	682	2.23	2.4	6.9	15.9	60	<0.1	0.6	0.2	15	1.12
DUP 1456547	QC		0.010	2.8	18.3	6.5	33	<0.1	8.0	6.8	689	2.27	2.4	3.5	15.7	60	<0.1	0.6	0.2	14	1.15
1419711	Rock	1.50	0.911	3.3	8.8	9.0	24	0.3	1.7	2.4	497	1.90	11.5	1336.5	10.9	51	<0.1	0.8	0.3	7	1.75
DUP 1419711	QC		0.789	3.1	9.0	8.2	23	0.2	1.9	2.5	474	1.86	10.9	360.1	10.1	48	<0.1	0.8	0.2	7	1.68
1456532	Rock	1.26	<0.005	3.3	16.4	12.3	33	<0.1	3.2	4.1	692	2.10	4.4	<0.5	10.9	78	<0.1	1.8	0.1	5	1.52
DUP 1456532	QC		0.007	3.2	17.3	12.8	35	<0.1	3.1	4.3	711	2.15	4.7	3.8	11.0	80	0.1	1.6	0.1	5	1.52
1456517	Rock	2.79	0.186	3.5	9.2	10.7	30	<0.1	2.2	3.5	555	2.04	2.4	168.2	10.5	94	<0.1	0.8	0.2	10	2.15
DUP 1456517	QC		0.148	3.1	8.7	10.4	29	<0.1	2.0	3.5	540	2.03	2.0	87.0	10.7	93	<0.1	0.8	0.2	10	2.12
Reference Materials																					
STD DS10	Standard			13.6	158.7	154.7	369	1.9	78.5	13.6	902	2.79	48.5	84.6	7.2	58	2.5	8.2	12.8	41	1.08
STD DS10	Standard			15.4	160.3	159.7	376	2.0	77.7	13.5	920	2.86	46.8	102.4	7.8	68	2.7	9.1	13.6	43	1.09



QUALITY CONTROL REPORT

WHI16000356.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1456544	Rock	0.068	12	3	0.09	1291	0.003	<20	0.51	0.023	0.25	0.1	0.10	5.3	0.1	<0.05	2	<0.5	<0.2
REP 1456544	QC	0.068	12	3	0.09	1319	0.002	<20	0.52	0.023	0.26	0.1	0.10	5.1	0.1	<0.05	2	<0.5	<0.2
1419686	Rock	0.040	12	5	0.08	719	0.002	<20	0.50	0.006	0.23	0.5	0.24	7.6	0.1	<0.05	2	<0.5	0.2
REP 1419686	QC																		
1419708	Rock	0.039	41	7	0.26	390	0.058	<20	0.63	0.046	0.45	0.7	0.08	3.3	0.3	<0.05	5	<0.5	<0.2
REP 1419708	QC	0.038	43	7	0.25	405	0.059	<20	0.61	0.046	0.44	0.7	0.08	3.4	0.3	<0.05	5	<0.5	<0.2
1419697	Rock	0.005	30	6	0.06	96	0.005	<20	0.27	0.038	0.17	1.3	0.07	1.3	<0.1	<0.05	2	<0.5	<0.2
REP 1419697	QC																		
1456528	Rock	0.015	14	4	0.05	922	0.002	<20	0.28	0.018	0.16	0.5	0.19	4.2	<0.1	<0.05	1	<0.5	<0.2
REP 1456528	QC	0.015	14	4	0.06	921	0.002	<20	0.28	0.019	0.16	0.5	0.17	4.1	<0.1	<0.05	1	<0.5	<0.2
1456514	Rock	0.008	22	5	0.04	290	0.002	<20	0.27	0.026	0.15	0.6	0.10	2.5	<0.1	<0.05	1	<0.5	<0.2
REP 1456514	QC	0.008	23	4	0.05	289	0.002	<20	0.27	0.026	0.15	0.8	0.11	2.5	<0.1	<0.05	1	<0.5	<0.2
1184627	Rock	0.059	17	40	0.75	1402	0.085	<20	0.98	0.051	0.37	1.7	0.10	7.2	0.2	<0.05	4	<0.5	<0.2
REP 1184627	QC																		
1184630	Rock	0.004	12	4	0.05	439	<0.001	<20	0.23	0.020	0.09	0.9	0.64	7.3	0.2	<0.05	<1	<0.5	<0.2
REP 1184630	QC																		
Core Reject Duplicates																			
1456547	Rock	0.049	26	10	0.13	424	0.011	<20	0.46	0.037	0.27	0.1	0.06	5.0	0.1	<0.05	2	<0.5	<0.2
DUP 1456547	QC	0.048	26	11	0.13	444	0.011	<20	0.45	0.036	0.26	0.2	0.06	5.1	0.1	<0.05	2	<0.5	<0.2
1419711	Rock	0.017	22	6	0.04	723	<0.001	<20	0.28	0.015	0.17	0.5	0.25	3.6	<0.1	<0.05	1	<0.5	<0.2
DUP 1419711	QC	0.016	21	6	0.04	654	<0.001	<20	0.32	0.017	0.19	0.4	0.25	3.6	<0.1	<0.05	1	<0.5	<0.2
1456532	Rock	0.027	15	5	0.05	1109	0.001	<20	0.30	0.014	0.16	0.2	0.11	2.4	<0.1	<0.05	<1	<0.5	<0.2
DUP 1456532	QC	0.029	15	6	0.05	1122	0.001	<20	0.33	0.017	0.17	0.2	0.11	2.4	<0.1	<0.05	<1	<0.5	<0.2
1456517	Rock	0.033	17	5	0.06	821	0.001	<20	0.31	0.017	0.18	0.3	0.11	3.3	<0.1	<0.05	1	<0.5	<0.2
DUP 1456517	QC	0.032	17	4	0.05	829	0.001	<20	0.31	0.019	0.18	0.3	0.12	3.1	<0.1	<0.05	1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.068	16	59	0.79	406	0.078	<20	1.04	0.069	0.34	2.8	0.27	2.6	5.4	0.28	4	1.9	5.1
STD DS10	Standard	0.084	18	58	0.81	443	0.084	<20	1.07	0.073	0.35	3.9	0.31	3.0	5.5	0.28	4	2.0	5.2



QUALITY CONTROL REPORT

WHI16000356.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			13.9	155.9	147.9	363	2.0	71.2	12.8	866	2.70	48.4	51.3	7.4	64	3.0	9.5	13.2	42	1.08
STD DS10	Standard			14.3	157.3	152.9	352	1.9	75.4	13.5	882	2.71	49.3	55.3	7.7	65	2.9	9.2	13.6	42	1.06
STD OREAS45EA	Standard			1.7	707.4	16.0	31	0.3	395.8	51.3	428	21.35	11.3	58.7	11.2	3	<0.1	0.4	0.3	320	0.03
STD OREAS45EA	Standard			1.6	698.3	15.4	30	0.3	396.1	54.3	442	21.46	10.3	57.5	10.7	4	<0.1	0.3	0.3	317	0.03
STD OREAS45EA	Standard			1.6	666.8	15.3	30	0.3	363.6	49.4	393	20.43	10.8	40.0	10.0	4	<0.1	0.4	0.3	277	0.03
STD OREAS45EA	Standard			1.7	700.2	16.0	32	0.3	405.0	55.0	418	22.36	12.1	45.9	10.9	5	<0.1	0.4	0.3	312	0.03
STD OXD108	Standard		0.413																		
STD OXD108	Standard		0.414																		
STD OXI121	Standard		1.786																		
STD OXI121	Standard		1.777																		
STD OXN117	Standard		7.418																		
STD OXN117	Standard		7.531																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	0.02	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.7	3.5	2.0	29	<0.1	1.2	3.9	422	1.73	0.8	<0.5	2.4	29	<0.1	<0.1	<0.1	22	0.67
ROCK-WHI	Prep Blank		<0.005	0.9	4.1	1.9	28	<0.1	1.4	3.8	409	1.75	0.9	<0.5	2.5	31	<0.1	<0.1	<0.1	23	0.58



QUALITY CONTROL REPORT

WHI16000356.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.089	18	53	0.77	401	0.078	<20	1.02	0.067	0.33	2.6	0.27	3.1	4.9	0.29	4	1.9	4.7
STD DS10	Standard	0.088	20	55	0.77	427	0.086	<20	1.03	0.070	0.33	3.1	0.27	3.2	5.0	0.28	4	2.2	5.3
STD OREAS45EA	Standard	0.026	8	883	0.10	163	0.095	<20	3.20	0.021	0.05	<0.1	0.02	74.7	<0.1	<0.05	14	0.5	<0.2
STD OREAS45EA	Standard	0.030	7	847	0.09	159	0.096	<20	3.21	0.021	0.05	<0.1	0.02	77.2	<0.1	<0.05	12	0.7	<0.2
STD OREAS45EA	Standard	0.031	7	790	0.10	155	0.096	<20	2.99	0.017	0.05	<0.1	<0.01	82.1	<0.1	<0.05	12	0.5	<0.2
STD OREAS45EA	Standard	0.035	8	842	0.10	172	0.109	<20	3.29	0.025	0.06	<0.1	0.01	86.0	<0.1	0.05	13	0.8	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	3	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.044	6	3	0.38	88	0.095	<20	0.97	0.125	0.12	0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.043	6	3	0.36	83	0.095	<20	0.89	0.102	0.10	0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: October 06, 2016
Report Date: November 01, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000357.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-10-06
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	132	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	138	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte	Unit	MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
			kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
1184663	Rock		2.85	<0.005	2.1	4.1	5.8	26	<0.1	5.0	6.2	416	1.82	5.7	4.1	8.0	751	<0.1	0.3	<0.1	29	2.15
1184664	Rock		2.85	<0.005	2.4	2.9	3.9	44	<0.1	6.6	8.7	791	2.84	25.6	3.6	12.3	187	<0.1	0.4	0.2	41	2.12
1184665	Rock		1.89	<0.005	1.9	3.5	2.4	45	<0.1	6.6	7.4	660	2.25	4.1	3.7	11.0	204	<0.1	0.1	0.2	39	1.55
1184666	Rock		2.27	0.097	2.1	2.5	9.6	34	<0.1	4.4	5.8	789	1.92	4.4	5.8	6.6	1196	<0.1	0.3	0.2	27	4.93
1184667	Rock		1.42	<0.005	2.0	3.2	4.2	34	<0.1	5.6	6.6	623	2.14	10.4	4.2	10.7	393	<0.1	0.3	0.2	30	2.19
1184668	Rock		2.05	<0.005	2.5	3.1	3.9	33	<0.1	6.4	6.8	655	2.34	12.6	7.5	10.4	288	<0.1	0.3	0.2	32	2.01
1184643	Rock		2.37	<0.005	1.5	3.4	3.7	44	<0.1	5.6	7.0	838	2.51	39.2	<0.5	12.4	156	<0.1	1.1	0.2	20	1.08
1184644	Rock		2.49	<0.005	1.2	2.4	2.5	34	<0.1	6.0	8.2	726	2.58	18.6	0.6	13.0	102	<0.1	1.1	0.3	25	1.11
1184645	Rock		2.55	<0.005	1.6	3.6	4.3	36	<0.1	6.0	7.1	801	2.93	113.8	6.2	9.4	126	<0.1	1.7	0.8	16	1.03
1184646	Rock		2.85	0.006	0.8	2.1	4.6	38	<0.1	4.6	7.1	669	2.69	29.4	7.0	6.3	169	<0.1	0.4	0.3	15	1.65
1184647	Rock		2.79	<0.005	2.3	5.8	7.3	45	<0.1	5.6	6.9	1207	2.84	159.1	4.2	6.4	161	<0.1	1.6	0.2	15	1.10
1184648	Rock		2.71	0.006	2.6	10.0	10.6	28	<0.1	14.9	4.2	545	2.01	106.1	7.4	7.6	127	<0.1	1.4	0.3	6	0.83
1184649	Rock		2.95	1.414	42.4	10.0	41.9	27	1.9	2.1	3.5	364	2.35	166.2	1146.1	8.0	116	0.1	2.2	0.9	4	0.94
1184650	Rock		0.53	0.012	0.2	2.4	2.0	15	<0.1	2.5	1.1	250	0.50	0.7	1.0	0.1	59	<0.1	<0.1	<0.1	6	19.89
1184651	Rock		3.69	0.051	3.2	4.8	5.7	31	<0.1	2.9	5.4	754	2.27	32.5	38.6	12.7	213	<0.1	0.8	0.3	12	2.27
1184652	Rock		3.15	0.019	1.9	3.2	3.9	36	<0.1	6.7	7.4	732	2.40	17.9	10.4	10.2	195	<0.1	0.6	0.3	35	1.69
1184633	Rock		2.54	<0.005	1.4	15.1	11.8	44	<0.1	14.2	8.5	603	2.37	43.9	3.6	8.5	118	<0.1	1.7	0.2	30	1.71
1184634	Rock		3.10	<0.005	1.6	11.7	14.3	48	<0.1	6.6	6.6	372	2.28	32.3	3.6	6.1	124	0.1	1.3	0.3	22	1.25
1184635	Rock		2.97	<0.005	1.4	5.3	7.1	30	<0.1	3.0	4.0	657	2.32	32.2	2.3	7.2	94	<0.1	0.6	0.5	11	1.06
1184636	Rock		2.19	<0.005	1.2	3.5	5.5	32	<0.1	3.1	5.2	726	2.70	21.8	2.9	6.7	123	<0.1	0.5	0.4	11	1.75
1184637	Rock		2.76	<0.005	1.1	2.5	7.6	28	<0.1	3.5	4.8	1220	3.50	26.9	2.3	6.2	148	<0.1	0.4	0.7	15	2.14
1184638	Rock		3.13	<0.005	0.8	2.1	11.3	21	<0.1	3.2	3.8	699	3.20	22.7	2.4	7.1	96	<0.1	0.3	0.9	11	1.65
1184639	Rock		2.24	<0.005	1.9	3.3	4.4	31	<0.1	3.5	7.3	802	2.35	55.6	1.9	9.5	69	<0.1	0.6	0.3	11	0.66
1184640	Rock Pulp		0.13	2.297	62.5	2182.0	1287.7	3802	27.1	177.6	21.0	644	5.21	1179.3	925.2	2.6	76	23.5	17.0	11.1	56	1.55
1184641	Rock		3.12	<0.005	1.0	2.9	5.0	36	<0.1	3.8	6.4	630	2.66	25.2	<0.5	8.1	81	<0.1	0.6	0.4	11	0.81
1184642	Rock		2.99	<0.005	1.6	3.3	5.1	33	<0.1	4.0	5.4	758	2.59	70.7	<0.5	6.7	70	<0.1	0.8	0.4	12	0.74
1184759	Rock		1.63	0.231	5.4	11.7	10.9	39	0.3	8.3	6.4	502	2.62	14.8	184.3	3.4	150	0.2	1.3	0.4	27	1.34
1184760	Rock		1.55	0.303	5.6	10.7	12.1	42	0.3	7.0	6.1	452	2.51	14.6	260.6	3.1	135	0.3	1.5	0.4	26	1.15
1184761	Rock		1.37	0.149	5.3	14.0	13.0	47	0.3	10.9	6.6	444	2.46	7.7	110.4	4.2	120	0.3	1.3	0.3	28	0.96
1184762	Rock		1.96	0.497	6.2	11.9	10.9	31	0.3	6.7	4.5	273	1.85	5.8	293.4	7.6	74	0.2	1.3	0.2	16	0.52



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1184663	Rock	0.045	20	20	0.61	1193	0.062	<20	0.64	0.042	0.49	1.7	0.02	5.8	0.2	0.11	4	<0.5	<0.2
1184664	Rock	0.066	33	25	1.00	726	0.095	<20	1.08	0.049	0.81	1.3	0.03	8.2	0.3	0.14	6	<0.5	<0.2
1184665	Rock	0.051	27	24	0.81	605	0.106	<20	1.06	0.055	0.80	2.0	0.04	6.6	0.3	0.14	6	<0.5	<0.2
1184666	Rock	0.039	20	18	0.62	2886	0.031	<20	0.56	0.051	0.36	1.8	0.12	5.7	0.1	0.15	3	<0.5	<0.2
1184667	Rock	0.049	24	17	0.66	1449	0.035	<20	0.54	0.044	0.39	0.7	0.08	8.1	0.1	0.11	3	<0.5	<0.2
1184668	Rock	0.050	22	22	0.71	1289	0.028	<20	0.61	0.058	0.41	1.8	0.09	9.1	0.2	0.10	3	<0.5	<0.2
1184643	Rock	0.052	29	24	0.44	2424	0.091	<20	0.92	0.038	0.72	0.6	0.05	8.9	0.3	0.08	5	<0.5	<0.2
1184644	Rock	0.053	38	32	0.55	901	0.105	<20	1.16	0.053	0.79	0.5	0.03	8.2	0.3	<0.05	6	<0.5	<0.2
1184645	Rock	0.053	18	17	0.20	1732	0.012	<20	0.59	0.021	0.36	0.5	0.47	10.8	0.3	0.06	3	<0.5	<0.2
1184646	Rock	0.036	7	11	0.23	1748	0.001	<20	0.45	0.031	0.23	0.3	0.26	11.4	0.2	0.10	1	<0.5	<0.2
1184647	Rock	0.046	10	13	0.12	3420	0.001	<20	0.33	0.032	0.17	0.5	0.43	10.3	0.5	0.12	1	<0.5	<0.2
1184648	Rock	0.016	11	37	0.12	2150	<0.001	<20	0.36	0.028	0.18	0.6	0.22	9.3	0.1	0.15	1	<0.5	<0.2
1184649	Rock	0.018	15	8	0.16	1532	<0.001	<20	0.28	0.025	0.15	1.7	0.43	4.6	0.1	0.33	1	<0.5	1.2
1184650	Rock	0.018	<1	<1	12.57	191	<0.001	<20	0.03	<0.001	0.02	<0.1	<0.01	0.6	<0.1	<0.05	<1	<0.5	<0.2
1184651	Rock	0.047	31	10	0.26	1796	0.023	<20	0.50	0.034	0.31	1.0	0.26	7.7	0.2	0.19	3	<0.5	<0.2
1184652	Rock	0.053	21	19	0.69	1011	0.047	<20	0.66	0.056	0.47	1.2	0.07	9.8	0.3	0.12	4	<0.5	<0.2
1184633	Rock	0.031	15	17	0.08	533	<0.001	<20	0.31	0.031	0.14	1.2	0.43	12.5	0.3	0.08	1	<0.5	<0.2
1184634	Rock	0.021	10	12	0.07	416	<0.001	<20	0.33	0.036	0.13	0.9	0.43	10.4	0.2	0.12	<1	<0.5	<0.2
1184635	Rock	0.033	10	6	0.06	387	<0.001	<20	0.32	0.030	0.13	1.0	0.26	11.8	0.3	<0.05	1	<0.5	<0.2
1184636	Rock	0.038	10	7	0.09	357	0.001	<20	0.43	0.032	0.19	0.6	0.28	12.9	0.4	0.07	2	<0.5	<0.2
1184637	Rock	0.021	8	7	0.12	305	<0.001	<20	0.42	0.016	0.18	0.9	0.39	12.2	0.8	0.09	1	<0.5	<0.2
1184638	Rock	0.034	8	7	0.11	203	<0.001	<20	0.48	0.017	0.22	0.6	0.31	12.9	0.3	0.12	2	<0.5	<0.2
1184639	Rock	0.015	12	9	0.08	237	0.001	<20	0.34	0.036	0.16	1.3	0.13	10.5	0.5	0.06	1	<0.5	<0.2
1184640	Rock Pulp	0.068	12	44	0.86	285	0.096	<20	1.49	0.081	0.19	8.1	0.74	4.8	1.3	1.56	6	3.4	0.6
1184641	Rock	0.027	12	10	0.12	413	0.002	<20	0.43	0.040	0.21	0.8	0.18	11.5	0.4	0.09	2	<0.5	<0.2
1184642	Rock	0.021	9	10	0.07	716	0.001	<20	0.34	0.024	0.18	0.6	0.29	12.5	0.5	<0.05	1	<0.5	<0.2
1184759	Rock	0.021	7	17	0.31	1683	0.004	<20	0.48	0.033	0.21	1.3	0.36	8.0	0.2	0.15	1	<0.5	0.3
1184760	Rock	0.021	7	12	0.28	1752	0.003	<20	0.35	0.021	0.14	1.0	0.38	8.6	0.2	0.14	1	<0.5	0.4
1184761	Rock	0.035	12	13	0.32	1958	0.012	<20	0.48	0.036	0.14	1.1	0.18	7.1	0.1	0.11	1	<0.5	0.3
1184762	Rock	0.026	17	8	0.18	1123	0.009	<20	0.37	0.030	0.14	1.0	0.10	4.3	<0.1	0.07	1	<0.5	0.4



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184763	Rock	1.93	0.132	3.4	14.5	5.5	26	0.2	4.4	3.6	381	1.60	9.6	388.4	6.2	110	0.1	1.6	0.3	11	0.38
1184764	Rock	3.10	0.050	3.4	15.0	3.9	31	<0.1	3.3	3.0	428	1.67	9.1	263.7	7.6	92	0.1	1.3	0.2	8	0.24
1184765	Rock	2.70	0.044	5.0	17.4	4.6	31	<0.1	3.2	3.5	571	2.00	12.8	54.8	8.0	88	<0.1	1.1	0.2	7	0.28
1184766	Rock	3.25	0.188	5.4	10.4	10.1	34	0.1	1.8	2.8	399	1.69	23.0	60.9	7.0	105	<0.1	1.1	0.2	11	0.19
1184767	Rock	2.81	0.413	5.3	11.4	8.3	29	0.5	2.0	2.9	464	1.70	7.9	277.3	7.4	98	0.2	1.5	0.2	11	0.85
1184768	Rock	2.56	0.096	3.2	9.9	5.9	34	0.2	1.8	2.7	421	1.86	7.8	101.7	10.1	117	0.2	0.9	<0.1	12	0.42
1184779	Rock	3.61	0.049	2.4	12.6	24.3	55	0.1	1.9	3.8	595	2.12	1.2	86.3	12.8	192	0.2	0.7	0.2	21	2.15
1184780	Rock	0.90	<0.005	0.1	3.0	2.0	14	<0.1	2.0	0.8	223	0.47	<0.5	2.3	0.2	50	<0.1	<0.1	<0.1	6	18.50
1184781	Rock	3.39	0.007	2.9	13.1	13.0	52	<0.1	4.9	4.5	579	1.50	0.9	4.4	16.7	424	0.2	0.8	<0.1	21	3.46
1184782	Rock	3.16	0.012	3.5	22.1	12.8	34	<0.1	2.5	3.1	613	1.30	1.4	3.7	13.3	548	0.2	0.5	<0.1	14	3.86
1184783	Rock	2.85	0.008	1.8	9.6	19.0	56	<0.1	2.2	4.9	683	1.66	0.6	2.8	10.5	248	0.2	0.2	<0.1	27	2.45
1184784	Rock	2.63	0.007	2.9	26.1	91.8	59	0.2	5.2	5.9	968	2.19	1.3	2.0	10.3	248	0.4	0.7	0.2	25	4.11
1184785	Rock	2.82	0.082	3.6	19.9	27.2	57	0.2	6.0	5.7	585	2.34	1.2	78.2	11.3	121	0.2	0.9	0.2	23	2.09
1184786	Rock	2.58	0.024	4.0	18.6	10.6	66	<0.1	3.0	6.5	601	2.57	1.7	26.0	10.7	133	0.1	0.5	<0.1	29	2.53
1184787	Rock	3.08	0.006	4.2	16.2	7.2	57	<0.1	6.5	7.1	688	2.67	1.3	3.7	13.0	90	<0.1	0.3	<0.1	34	2.31
1184788	Rock	2.95	0.006	2.9	15.3	4.2	63	<0.1	5.2	7.2	624	2.71	0.6	5.2	12.1	49	<0.1	0.1	<0.1	42	1.47
1184799	Rock	2.14	0.484	4.7	20.0	5.6	45	0.4	2.2	6.0	548	2.84	<0.5	660.9	9.9	85	0.1	0.1	0.1	21	1.57
1184800	Rock Pulp	0.09	2.319	66.6	2166.7	1304.7	3685	26.0	179.0	19.5	647	5.34	1187.3	755.0	2.6	71	21.5	15.9	9.2	56	1.49
1184801	Rock	1.86	0.104	2.7	24.1	9.7	54	0.1	3.6	5.9	626	2.63	0.8	90.4	11.3	93	0.1	0.1	0.2	26	1.76
1184802	Rock	2.35	0.071	2.1	11.3	5.0	45	<0.1	2.3	3.1	408	1.60	<0.5	24.6	8.6	83	<0.1	<0.1	<0.1	36	1.07
1184803	Rock	1.91	0.017	2.3	7.7	3.2	43	<0.1	3.0	5.0	434	2.16	<0.5	5.9	10.1	40	<0.1	<0.1	0.2	19	0.91
1184804	Rock	2.26	0.005	2.3	7.3	3.2	48	<0.1	1.9	4.5	450	2.15	<0.5	2.6	11.5	33	<0.1	<0.1	<0.1	13	0.62
1184805	Rock	2.07	0.008	2.3	11.8	4.9	47	<0.1	2.4	4.0	412	1.89	<0.5	15.2	14.4	42	<0.1	<0.1	<0.1	14	0.63
1184806	Rock	3.35	<0.005	2.5	19.5	4.3	58	<0.1	2.6	5.5	501	2.53	<0.5	<0.5	11.9	58	<0.1	<0.1	<0.1	23	0.93
1184807	Rock	2.29	0.006	2.7	14.5	4.0	53	<0.1	2.4	5.4	554	2.66	<0.5	0.6	13.6	40	<0.1	<0.1	<0.1	16	0.85
1184769	Rock	3.12	0.125	4.6	6.4	7.8	42	0.3	2.0	2.9	406	2.06	7.2	103.8	9.4	116	0.1	0.7	<0.1	17	0.44
1184770	Rock Pulp	0.12	0.854	4.3	34.2	5.4	50	0.2	24.9	9.1	402	2.50	6.1	625.8	1.0	36	0.1	0.8	0.1	60	0.81
1184771	Rock	2.80	0.101	3.3	5.5	5.9	42	0.2	1.9	2.7	406	1.68	4.4	60.0	11.3	100	0.3	0.6	<0.1	17	1.00
1184772	Rock	2.74	0.165	4.1	10.5	11.1	39	0.3	2.1	3.2	405	2.04	12.4	108.3	6.3	161	0.2	1.2	<0.1	25	1.09
1184773	Rock	3.63	0.202	2.7	6.6	18.5	33	0.2	1.6	2.8	320	1.86	5.7	101.8	6.0	155	0.1	0.5	<0.1	20	0.87



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1184763	Rock	0.015	11	6	0.11	2976	0.003	<20	0.34	0.018	0.18	1.4	0.18	3.8	<0.1	0.10	<1	<0.5	<0.2
1184764	Rock	0.011	10	6	0.08	2240	0.002	<20	0.35	0.018	0.20	1.1	0.10	2.9	0.1	0.06	<1	<0.5	<0.2
1184765	Rock	0.011	10	6	0.09	2017	0.002	<20	0.39	0.012	0.24	1.2	0.11	3.6	0.1	0.06	1	<0.5	<0.2
1184766	Rock	0.010	9	3	0.05	3050	<0.001	<20	0.30	0.001	0.20	0.8	0.18	3.2	<0.1	0.09	<1	<0.5	<0.2
1184767	Rock	0.007	8	4	0.31	1618	<0.001	<20	0.24	0.007	0.15	0.9	0.11	3.5	<0.1	0.22	<1	<0.5	0.4
1184768	Rock	0.010	16	4	0.18	2702	<0.001	<20	0.25	0.034	0.15	1.0	0.19	2.8	<0.1	0.15	<1	<0.5	<0.2
1184779	Rock	0.057	20	7	0.32	1395	0.008	<20	0.21	0.060	0.11	4.1	0.03	3.2	<0.1	0.22	<1	<0.5	<0.2
1184780	Rock	0.014	<1	<1	12.08	355	0.001	<20	0.04	0.002	0.02	0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1184781	Rock	0.038	20	15	0.38	2320	0.015	<20	0.27	0.047	0.21	3.6	0.02	3.5	0.1	0.24	2	<0.5	<0.2
1184782	Rock	0.031	17	10	0.20	2726	0.005	<20	0.18	0.046	0.12	4.8	0.02	2.6	<0.1	0.23	<1	<0.5	<0.2
1184783	Rock	0.042	18	8	0.32	1505	0.019	<20	0.24	0.077	0.16	4.5	0.02	2.6	<0.1	0.28	2	<0.5	<0.2
1184784	Rock	0.048	13	17	0.46	329	0.022	<20	0.33	0.050	0.25	4.1	0.11	3.8	0.1	1.04	2	0.8	0.2
1184785	Rock	0.048	14	9	0.58	455	0.006	<20	0.23	0.058	0.16	5.9	0.05	4.7	<0.1	0.91	1	<0.5	0.3
1184786	Rock	0.055	17	11	0.65	1054	0.010	<20	0.38	0.040	0.26	3.0	0.03	6.0	<0.1	0.33	2	<0.5	<0.2
1184787	Rock	0.050	30	24	0.67	328	0.096	<20	0.99	0.036	0.82	2.1	0.01	4.8	0.3	0.36	5	0.6	<0.2
1184788	Rock	0.059	29	23	0.84	319	0.138	<20	1.22	0.047	1.01	2.8	<0.01	4.7	0.4	0.33	7	<0.5	<0.2
1184799	Rock	0.079	30	10	0.66	544	0.091	<20	0.84	0.057	0.55	5.5	0.05	3.4	0.2	0.70	4	<0.5	0.3
1184800	Rock Pulp	0.057	10	45	0.85	230	0.087	<20	1.49	0.081	0.19	8.0	0.73	4.0	1.3	1.52	5	4.0	0.5
1184801	Rock	0.055	29	12	0.63	463	0.045	<20	0.57	0.048	0.34	4.8	0.02	4.4	0.2	0.51	3	<0.5	<0.2
1184802	Rock	0.030	21	11	0.34	164	0.056	<20	0.48	0.060	0.28	6.6	<0.01	1.9	0.1	0.18	3	<0.5	<0.2
1184803	Rock	0.046	32	13	0.68	214	0.109	<20	1.03	0.053	0.73	4.8	<0.01	2.0	0.3	0.23	5	<0.5	<0.2
1184804	Rock	0.036	34	11	0.49	252	0.115	<20	0.94	0.058	0.67	5.3	<0.01	1.9	0.3	0.18	5	<0.5	<0.2
1184805	Rock	0.031	32	13	0.36	258	0.086	<20	0.73	0.056	0.48	7.2	<0.01	1.5	0.3	0.15	5	<0.5	<0.2
1184806	Rock	0.056	32	14	0.48	335	0.111	<20	0.98	0.054	0.60	5.4	<0.01	1.7	0.3	0.24	6	<0.5	<0.2
1184807	Rock	0.058	42	13	0.60	311	0.154	<20	1.19	0.057	0.76	7.8	<0.01	2.0	0.3	0.16	7	<0.5	<0.2
1184769	Rock	0.023	15	4	0.14	2478	<0.001	<20	0.27	0.030	0.15	0.8	0.18	4.8	0.1	0.15	<1	<0.5	0.3
1184770	Rock Pulp	0.051	4	35	0.72	87	0.130	<20	1.50	0.083	0.13	10.6	0.05	4.7	<0.1	<0.05	5	<0.5	<0.2
1184771	Rock	0.017	20	4	0.22	1865	<0.001	<20	0.21	0.047	0.11	0.8	0.11	4.8	<0.1	0.15	<1	<0.5	<0.2
1184772	Rock	0.013	10	4	0.19	2770	<0.001	<20	0.25	0.014	0.14	0.9	0.32	4.9	0.1	0.22	<1	<0.5	0.2
1184773	Rock	0.021	6	4	0.21	2630	<0.001	<20	0.24	0.022	0.12	0.8	0.22	3.4	0.1	0.19	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184774	Rock	2.81	0.098	4.9	23.5	18.8	42	0.4	1.8	3.3	483	2.07	3.9	64.6	5.3	96	0.3	2.7	0.1	13	0.58
1184775	Rock	3.46	0.168	3.7	19.8	39.9	61	0.3	21.8	12.4	732	3.02	6.3	120.8	5.5	178	0.2	2.3	<0.1	40	3.27
1184776	Rock	2.48	0.198	2.1	14.6	20.1	64	1.0	2.5	6.0	625	2.57	1.8	224.5	10.2	103	0.2	1.2	<0.1	23	1.72
1184777	Rock	2.63	0.082	2.2	11.6	13.8	51	0.4	1.7	5.5	523	2.54	1.0	70.6	10.2	112	0.2	0.8	<0.1	24	1.87
1184778	Rock	3.41	0.028	2.8	5.5	10.3	46	<0.1	3.1	4.5	391	2.00	1.1	22.9	12.0	109	<0.1	0.7	<0.1	26	1.59
1184789	Rock	1.98	0.013	3.2	15.5	13.0	43	<0.1	2.3	4.5	508	1.93	<0.5	9.9	12.6	78	<0.1	0.2	<0.1	19	1.53
1184790	Rock	1.56	0.012	3.1	17.7	11.0	42	<0.1	2.4	4.5	499	2.01	0.8	6.7	12.3	76	<0.1	0.2	<0.1	20	1.35
1184791	Rock	2.61	0.318	8.5	9.0	17.1	50	0.6	2.2	4.9	470	2.03	1.2	247.0	11.3	141	0.3	0.5	0.2	19	1.87
1184792	Rock	3.81	0.022	1.3	2.3	3.4	20	<0.1	1.4	3.0	356	1.60	0.6	11.9	16.0	142	<0.1	0.2	<0.1	7	1.18
1184793	Rock	1.80	0.067	1.4	5.1	6.3	39	0.2	1.3	3.7	435	1.78	0.6	85.8	7.6	257	0.3	0.3	<0.1	21	2.35
1184794	Rock	2.16	0.045	3.0	5.6	3.5	38	<0.1	1.8	4.5	545	2.27	<0.5	25.5	12.0	57	<0.1	0.1	<0.1	20	1.57
1184795	Rock	2.90	0.037	1.4	2.7	1.9	27	<0.1	1.5	3.5	357	1.56	<0.5	4.9	9.4	58	<0.1	<0.1	<0.1	15	1.01
1184796	Rock	2.35	0.008	1.5	3.6	1.8	27	<0.1	1.8	3.5	531	1.59	<0.5	<0.5	9.1	47	<0.1	<0.1	<0.1	14	1.91
1184797	Rock	2.57	0.031	2.9	20.9	3.5	36	<0.1	1.8	5.5	462	2.39	0.6	10.9	10.3	53	<0.1	<0.1	<0.1	19	1.27
1184798	Rock	1.55	0.348	7.8	7.8	6.9	30	0.3	1.8	3.8	340	1.69	0.8	220.9	12.7	107	0.2	0.2	0.1	16	1.21
1184679	Rock	2.20	0.009	2.1	2.1	5.1	22	<0.1	6.6	5.6	760	2.43	33.3	8.2	5.1	185	<0.1	0.7	0.2	21	3.32
1184680	Rock	0.64	<0.005	<0.1	0.9	1.3	13	<0.1	0.9	0.4	207	0.42	<0.5	<0.5	0.1	47	<0.1	<0.1	<0.1	5	18.40
1184681	Rock	2.11	0.052	2.5	3.7	5.5	13	<0.1	3.2	2.9	533	1.70	175.4	21.6	4.8	122	<0.1	1.0	0.2	7	1.74
1184682	Rock	2.13	3.270	5.2	37.1	7.8	23	1.8	3.8	4.9	664	1.95	54.9	2809.6	3.3	102	0.1	10.7	0.9	5	1.64
1184683	Rock	2.50	0.878	3.6	12.3	5.8	19	0.3	3.5	4.9	618	2.01	19.3	911.4	3.6	132	<0.1	2.3	0.2	6	1.85
1184684	Rock	2.24	1.364	15.9	3.0	3.9	16	0.3	3.0	4.7	617	1.85	15.9	1290.0	3.0	129	<0.1	0.8	0.3	8	1.79
1184685	Rock	2.27	2.202	12.8	14.8	5.4	22	0.5	5.2	6.3	854	2.28	7.5	2286.0	3.1	202	<0.1	3.5	0.3	10	2.80
1184686	Rock	2.39	0.278	2.1	6.8	3.9	21	0.1	3.9	5.5	583	1.69	15.1	245.9	2.0	160	<0.1	1.4	0.2	10	2.28
1184687	Rock	2.45	0.047	1.2	8.9	4.4	26	<0.1	3.5	6.6	810	2.22	11.6	30.4	3.4	216	<0.1	1.8	<0.1	18	3.01
1184688	Rock	2.63	3.501	27.1	16.4	6.9	18	1.7	6.9	5.3	461	1.76	5.5	4528.9	2.4	122	<0.1	5.1	0.7	5	1.72
1184709	Rock	2.59	0.391	2.9	18.8	25.2	47	1.2	3.6	5.9	428	2.41	7.5	395.0	3.5	169	0.1	2.0	0.3	12	2.08
1184710	Rock Pulp	0.12	0.826	4.4	33.4	4.9	49	0.3	24.1	9.3	401	2.50	5.0	539.4	0.9	38	0.2	0.7	0.1	59	0.78
1184711	Rock	2.56	0.312	3.2	15.8	20.6	51	1.0	4.7	8.9	864	2.99	11.4	357.4	3.7	127	0.2	1.1	0.3	22	2.21
1184712	Rock	2.57	0.066	2.6	9.6	16.2	62	0.2	3.8	5.3	597	2.61	14.7	38.3	3.0	218	<0.1	0.5	0.3	16	2.11
1184713	Rock	2.62	0.498	2.8	23.9	32.2	71	1.7	13.9	9.1	965	3.62	14.5	527.3	2.7	201	0.2	0.7	0.2	40	2.59



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1184774	Rock	0.016	5	3	0.16	1200	<0.001	<20	0.31	0.014	0.17	0.5	0.12	4.2	0.2	0.11	<1	<0.5	<0.2
1184775	Rock	0.026	5	30	0.92	1652	0.003	<20	0.51	0.022	0.31	0.6	0.17	9.6	0.2	0.33	2	<0.5	0.2
1184776	Rock	0.073	12	5	0.34	489	0.010	<20	0.29	0.044	0.19	2.3	0.06	5.6	<0.1	1.04	1	<0.5	0.7
1184777	Rock	0.059	13	5	0.38	457	0.009	<20	0.24	0.058	0.14	3.8	0.02	4.8	<0.1	0.97	1	<0.5	0.3
1184778	Rock	0.040	14	9	0.37	1043	0.002	<20	0.19	0.058	0.10	3.8	0.02	4.2	<0.1	0.52	<1	<0.5	<0.2
1184789	Rock	0.037	26	9	0.43	555	0.054	<20	0.52	0.050	0.37	4.4	0.02	2.8	0.1	0.50	4	<0.5	<0.2
1184790	Rock	0.040	30	10	0.44	514	0.068	<20	0.63	0.056	0.44	5.4	<0.01	2.7	0.2	0.52	4	<0.5	<0.2
1184791	Rock	0.038	20	9	0.46	762	0.015	<20	0.27	0.066	0.18	4.9	0.06	4.1	<0.1	0.62	1	<0.5	0.5
1184792	Rock	0.026	32	8	0.26	608	0.035	<20	0.41	0.045	0.29	3.8	<0.01	1.2	0.1	0.14	2	<0.5	<0.2
1184793	Rock	0.059	13	7	0.50	981	0.005	<20	0.23	0.035	0.17	1.9	0.03	3.2	<0.1	0.22	<1	<0.5	<0.2
1184794	Rock	0.057	31	9	0.51	333	0.108	<20	0.86	0.046	0.69	3.6	0.01	3.4	0.3	0.15	5	<0.5	<0.2
1184795	Rock	0.040	25	8	0.43	618	0.092	<20	0.74	0.044	0.51	4.0	<0.01	1.8	0.2	0.13	4	<0.5	<0.2
1184796	Rock	0.040	25	9	0.51	266	0.091	<20	0.79	0.040	0.55	4.0	<0.01	1.6	0.2	0.15	5	<0.5	<0.2
1184797	Rock	0.049	30	10	0.51	323	0.098	<20	0.85	0.055	0.60	4.8	0.01	2.0	0.2	0.39	5	<0.5	<0.2
1184798	Rock	0.036	25	10	0.35	578	0.033	<20	0.35	0.056	0.24	5.6	0.03	2.6	0.1	0.46	2	<0.5	0.2
1184679	Rock	0.041	8	11	0.50	1069	<0.001	<20	0.34	0.002	0.23	0.7	0.36	8.6	<0.1	0.06	<1	<0.5	<0.2
1184680	Rock	0.012	<1	<1	11.79	23	<0.001	<20	0.03	<0.001	0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1184681	Rock	0.009	8	6	0.20	1602	<0.001	<20	0.28	0.001	0.22	1.9	0.32	5.1	0.1	0.09	<1	<0.5	<0.2
1184682	Rock	0.018	10	5	0.12	1376	<0.001	<20	0.20	0.001	0.19	2.0	2.73	5.3	<0.1	0.27	<1	<0.5	1.2
1184683	Rock	0.024	9	5	0.35	864	<0.001	<20	0.27	0.001	0.25	1.1	1.22	6.7	<0.1	0.45	<1	<0.5	0.2
1184684	Rock	0.023	7	5	0.33	1063	<0.001	<20	0.24	0.001	0.24	1.2	0.99	6.8	0.1	0.39	<1	<0.5	0.2
1184685	Rock	0.024	7	6	0.87	522	<0.001	<20	0.26	0.001	0.23	1.0	1.19	8.6	<0.1	0.65	<1	<0.5	0.3
1184686	Rock	0.014	5	6	0.56	1448	<0.001	<20	0.27	0.003	0.23	0.7	0.31	6.7	<0.1	0.20	<1	<0.5	<0.2
1184687	Rock	0.035	8	7	0.84	1918	<0.001	<20	0.30	0.005	0.27	0.8	0.85	7.9	<0.1	0.17	<1	<0.5	<0.2
1184688	Rock	0.017	6	9	0.55	534	<0.001	<20	0.18	0.002	0.15	3.1	0.64	5.8	<0.1	0.61	<1	<0.5	0.7
1184709	Rock	0.009	4	8	0.70	417	<0.001	<20	0.20	0.030	0.12	0.7	0.36	8.8	0.2	1.08	<1	0.5	0.9
1184710	Rock Pulp	0.057	4	32	0.72	95	0.119	<20	1.50	0.084	0.13	10.8	0.05	4.7	<0.1	<0.05	5	<0.5	<0.2
1184711	Rock	0.008	5	12	0.86	367	<0.001	<20	0.23	0.030	0.14	1.0	0.31	10.4	0.2	1.14	<1	0.8	0.8
1184712	Rock	0.034	4	11	0.68	1230	<0.001	<20	0.36	0.009	0.24	0.6	0.37	9.4	0.2	0.36	1	<0.5	<0.2
1184713	Rock	0.032	3	21	1.04	413	<0.001	<20	0.32	0.005	0.19	0.8	0.43	12.9	0.2	0.93	<1	<0.5	1.3



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 5 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184714	Rock	2.69	0.109	2.2	16.8	22.5	61	0.4	6.9	6.3	594	2.35	16.1	98.4	1.9	169	0.1	0.4	0.1	29	2.39
1184715	Rock	2.83	0.081	2.2	15.5	12.1	66	0.3	7.1	6.5	559	2.32	12.1	75.3	4.3	184	0.2	0.7	0.2	29	2.76
1184716	Rock	2.51	0.034	2.6	19.9	11.9	66	0.2	7.4	5.1	479	2.13	11.6	40.1	4.0	219	0.2	1.2	<0.1	25	2.60
1184717	Rock	2.73	0.034	2.1	7.8	14.0	54	0.2	6.6	5.7	495	2.04	5.4	31.1	2.7	174	0.2	0.5	0.1	23	2.27
1184718	Rock	3.02	0.350	2.6	5.9	24.9	36	1.3	4.1	4.9	725	3.17	7.5	361.1	2.8	188	0.4	0.3	0.2	35	2.75
1184689	Rock	2.13	0.156	5.0	4.5	4.6	36	0.1	6.1	5.9	816	2.49	16.4	412.3	4.2	214	<0.1	1.3	0.4	24	2.50
1184690	Rock	1.23	0.098	4.8	4.4	5.1	37	<0.1	6.5	5.9	816	2.55	18.0	119.0	4.7	219	<0.1	1.3	0.4	24	2.58
1184691	Rock	2.68	0.043	1.9	3.7	4.7	35	<0.1	6.2	6.8	659	2.52	5.9	15.2	4.0	315	<0.1	0.5	0.3	24	2.74
1184692	Rock	2.62	0.267	1.6	5.1	4.8	30	<0.1	6.1	6.7	591	2.35	12.0	77.2	5.6	305	<0.1	1.0	0.3	24	2.74
1184693	Rock	2.53	0.018	1.8	4.7	4.6	27	<0.1	5.3	6.0	464	2.21	22.2	10.9	5.0	267	<0.1	0.9	0.5	20	2.33
1184694	Rock	2.51	0.274	7.5	18.7	8.3	31	0.3	9.9	10.9	512	2.96	78.8	212.1	4.0	219	<0.1	4.5	0.7	22	2.55
1184695	Rock	2.54	0.258	7.1	8.9	5.3	30	0.2	5.6	5.4	482	2.39	8.7	218.2	5.7	175	<0.1	1.8	0.3	15	2.15
1184696	Rock	2.49	0.243	3.4	4.5	3.9	33	<0.1	2.0	3.9	688	2.25	8.4	371.7	6.7	166	<0.1	0.8	<0.1	20	1.78
1184697	Rock	2.28	0.125	4.3	6.6	4.1	26	<0.1	1.7	3.8	684	1.88	6.7	92.7	9.8	139	0.1	0.7	<0.1	14	1.32
1184698	Rock	2.62	0.587	6.1	6.6	5.6	24	0.3	1.3	3.1	492	1.88	10.1	973.9	3.8	111	<0.1	0.9	0.2	9	0.89
1184719	Rock	2.48	0.095	7.0	8.3	15.9	34	0.3	3.9	3.8	469	1.95	5.2	82.0	8.8	146	0.6	0.2	0.2	15	1.21
1184720	Rock	0.65	<0.005	<0.1	2.1	1.4	14	<0.1	1.7	0.6	201	0.40	<0.5	<0.5	<0.1	46	<0.1	<0.1	<0.1	<2	18.76
1184721	Rock	2.17	0.349	5.7	13.4	16.9	38	1.0	3.1	4.3	490	2.62	2.2	331.5	11.4	134	0.3	0.3	0.5	15	1.66
1184722	Rock	2.45	0.046	3.5	7.5	8.4	40	<0.1	1.6	4.4	460	2.34	3.0	22.9	11.3	155	<0.1	0.4	0.2	14	1.49
1184723	Rock	1.57	0.131	2.5	5.5	35.9	45	0.4	1.8	4.6	592	2.26	4.0	150.5	9.5	127	0.2	0.4	0.2	17	1.75
1184724	Rock	1.54	0.107	3.0	6.9	25.2	37	0.3	1.8	3.7	437	1.96	5.6	90.5	8.2	110	0.1	0.3	0.1	13	1.43
1184725	Rock	1.20	0.157	2.2	9.7	24.6	31	0.6	2.1	3.6	477	2.08	7.9	227.7	6.9	138	0.1	0.7	0.2	11	1.52
1184726	Rock	2.06	0.067	2.0	7.9	12.1	27	0.2	1.2	2.2	489	1.65	5.1	49.6	11.5	132	<0.1	0.7	<0.1	10	1.58
1184727	Rock	3.29	0.107	2.4	9.9	13.1	28	0.3	1.7	3.3	514	1.83	3.4	74.0	11.8	126	<0.1	0.6	<0.1	16	1.66
1184728	Rock	2.44	0.041	1.0	5.3	11.8	41	0.1	1.2	4.3	653	2.31	3.1	54.4	8.8	194	0.1	0.1	<0.1	23	2.79
1184699	Rock	2.50	1.361	2.2	13.3	6.1	39	0.2	1.8	3.9	481	2.28	18.4	312.8	3.4	115	<0.1	1.6	0.3	12	1.44
1184700	Rock Pulp	0.12	2.396	66.3	2244.5	1308.5	3630	26.8	183.2	19.3	621	5.09	1182.0	3167.9	2.9	73	19.3	13.8	10.5	55	1.47
1184701	Rock	2.64	0.464	1.6	16.9	4.5	49	0.1	1.4	4.2	670	3.08	3.2	363.4	3.9	141	0.1	1.4	0.1	13	1.55
1184702	Rock	2.32	0.309	3.2	12.8	9.1	37	0.3	2.1	5.3	639	3.20	33.6	772.1	2.7	141	0.1	0.8	0.3	9	1.67
1184703	Rock	2.38	0.232	2.9	5.0	3.6	34	<0.1	4.5	6.2	669	2.27	6.1	41.6	2.8	142	<0.1	0.3	0.2	12	2.53



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 5 of 6 Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Ti ppm	S %	Ga ppm	Se ppm	Te ppm	
1184714	Rock	0.029	3	18	0.88	857	<0.001	<20	0.29	0.003	0.17	1.0	0.40	9.5	0.3	0.33	<1	<0.5	0.3
1184715	Rock	0.043	7	20	1.09	544	<0.001	<20	0.28	0.038	0.16	1.6	0.38	11.0	0.5	0.39	<1	<0.5	0.2
1184716	Rock	0.057	8	21	0.87	629	<0.001	<20	0.29	0.040	0.15	1.0	0.27	11.2	0.1	0.20	<1	<0.5	<0.2
1184717	Rock	0.044	5	19	0.72	468	<0.001	<20	0.28	0.031	0.15	0.9	0.18	11.3	0.2	0.46	<1	<0.5	<0.2
1184718	Rock	0.027	3	13	0.91	130	<0.001	<20	0.23	0.034	0.13	1.3	0.19	9.4	0.2	1.51	<1	<0.5	1.1
1184689	Rock	0.028	10	15	0.56	2106	<0.001	<20	0.30	0.019	0.21	0.7	0.55	10.4	<0.1	0.15	<1	<0.5	<0.2
1184690	Rock	0.031	10	15	0.56	2244	<0.001	<20	0.29	0.020	0.22	0.6	0.53	10.3	<0.1	0.15	<1	<0.5	<0.2
1184691	Rock	0.035	11	18	0.96	1058	0.001	<20	0.32	0.028	0.22	0.5	0.46	11.4	<0.1	0.17	1	<0.5	<0.2
1184692	Rock	0.038	14	17	1.03	1249	0.002	<20	0.29	0.031	0.20	0.7	0.41	9.5	<0.1	0.19	1	<0.5	<0.2
1184693	Rock	0.042	11	15	0.84	615	0.002	<20	0.31	0.029	0.20	0.7	0.34	9.6	<0.1	0.22	1	<0.5	<0.2
1184694	Rock	0.051	9	14	0.88	464	0.001	<20	0.25	0.033	0.15	0.8	0.42	11.3	<0.1	0.31	<1	<0.5	0.5
1184695	Rock	0.038	12	11	0.75	1323	<0.001	<20	0.18	0.037	0.12	1.2	0.23	9.1	<0.1	0.40	<1	<0.5	0.3
1184696	Rock	0.067	7	11	0.52	1824	0.002	<20	0.21	0.045	0.13	1.6	0.24	7.9	<0.1	0.21	<1	<0.5	<0.2
1184697	Rock	0.056	4	8	0.34	1661	<0.001	<20	0.23	0.032	0.14	0.7	0.41	6.1	<0.1	0.11	<1	<0.5	<0.2
1184698	Rock	0.025	8	7	0.21	1261	<0.001	<20	0.24	0.014	0.16	1.1	0.27	5.6	<0.1	0.36	<1	<0.5	<0.2
1184719	Rock	0.026	12	12	0.46	204	0.001	<20	0.16	0.047	0.08	2.9	0.19	4.8	<0.1	0.65	<1	<0.5	0.5
1184720	Rock	0.012	<1	<1	11.50	21	<0.001	<20	0.03	<0.001	0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1184721	Rock	0.032	12	10	0.51	64	<0.001	<20	0.20	0.052	0.12	2.4	0.07	4.3	<0.1	1.40	<1	<0.5	1.1
1184722	Rock	0.042	17	11	0.41	522	0.003	<20	0.32	0.035	0.22	1.2	0.05	4.8	<0.1	0.62	1	<0.5	<0.2
1184723	Rock	0.041	9	9	0.55	164	<0.001	<20	0.21	0.038	0.12	0.8	0.11	6.3	<0.1	0.99	<1	<0.5	0.4
1184724	Rock	0.020	9	10	0.42	253	<0.001	<20	0.23	0.026	0.14	0.3	0.11	4.6	<0.1	0.77	<1	<0.5	0.2
1184725	Rock	0.021	7	6	0.44	381	<0.001	<20	0.23	0.023	0.14	1.0	0.18	4.5	<0.1	0.75	<1	<0.5	0.5
1184726	Rock	0.017	9	6	0.49	1329	<0.001	<20	0.19	0.031	0.12	0.4	0.13	4.1	<0.1	0.29	<1	<0.5	<0.2
1184727	Rock	0.027	11	7	0.48	874	0.001	<20	0.19	0.037	0.12	1.0	0.08	4.4	<0.1	0.45	<1	<0.5	<0.2
1184728	Rock	0.047	9	3	0.66	1092	0.001	<20	0.29	0.019	0.22	0.2	0.05	5.6	<0.1	0.40	<1	0.5	<0.2
1184699	Rock	0.030	8	8	0.43	752	<0.001	<20	0.28	0.018	0.21	0.8	0.41	7.5	<0.1	0.42	<1	<0.5	<0.2
1184700	Rock Pulp	0.061	11	44	0.84	189	0.082	<20	1.47	0.079	0.19	8.5	0.79	3.8	1.3	1.53	5	2.7	0.6
1184701	Rock	0.045	9	7	0.47	1056	0.001	<20	0.27	0.024	0.22	1.0	0.57	8.8	<0.1	0.50	<1	<0.5	<0.2
1184702	Rock	0.031	4	6	0.51	419	<0.001	<20	0.34	0.005	0.26	0.5	0.87	10.0	0.1	0.74	<1	<0.5	0.3
1184703	Rock	0.004	4	7	0.75	747	<0.001	<20	0.31	0.003	0.28	0.3	0.24	7.1	<0.1	0.16	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1184704	Rock	2.54	0.043	1.1	4.3	5.2	37	<0.1	4.5	6.3	719	2.43	3.6	38.5	2.8	243	0.1	0.4	<0.1	14	2.79
1184705	Rock	2.49	0.489	2.7	45.6	5.8	57	0.6	7.1	7.5	675	2.58	6.7	1783.6	6.0	201	0.2	5.9	0.3	17	2.77
1184706	Rock	2.52	0.202	1.6	14.5	7.1	53	0.4	7.2	6.2	923	2.37	4.3	372.4	5.6	187	0.2	2.2	0.1	19	2.58
1184707	Rock	3.32	0.766	1.9	11.7	38.5	59	2.2	11.6	8.9	907	2.50	7.2	667.3	5.7	166	0.3	2.1	0.2	15	2.22
1184708	Rock	2.85	1.570	1.5	7.4	40.1	33	4.5	5.1	7.3	689	2.55	10.7	1490.5	8.2	153	0.2	0.4	0.3	7	1.86
1184669	Rock	1.35	0.009	1.1	17.4	5.8	43	<0.1	16.0	9.1	561	2.65	29.0	2.3	7.2	56	0.2	0.7	0.5	39	0.62
1184670	Rock Pulp	0.12	0.849	4.4	33.8	5.3	49	0.3	24.7	9.6	398	2.50	5.7	1019.4	1.1	39	0.2	0.7	0.1	60	0.81
1184671	Rock	2.64	0.008	1.6	17.6	8.0	44	<0.1	16.5	9.9	580	2.89	35.7	3.6	6.5	69	<0.1	0.7	0.6	39	0.64
1184672	Rock	1.44	0.015	1.5	17.2	6.2	45	<0.1	17.0	9.5	539	2.47	24.6	5.6	5.7	61	0.2	0.7	0.4	37	1.08
1184673	Rock	1.89	0.111	1.8	9.3	6.2	36	<0.1	9.2	7.2	623	2.09	11.7	54.7	6.3	317	0.1	0.6	0.1	23	3.21
1184674	Rock	2.29	0.016	1.4	5.1	4.2	41	<0.1	8.9	7.2	683	2.38	16.8	10.6	8.8	143	<0.1	0.5	0.3	39	1.55
1184675	Rock	3.34	0.018	1.9	4.6	2.8	29	<0.1	6.5	6.1	582	2.18	74.7	8.8	6.7	165	<0.1	0.8	0.1	26	1.33
1184676	Rock	2.01	<0.005	2.3	3.7	4.2	38	<0.1	5.1	7.6	1011	2.98	27.3	1.6	5.0	138	<0.1	0.3	0.3	37	2.99
1184677	Rock	2.47	<0.005	2.1	3.6	3.0	31	<0.1	5.0	6.1	693	2.33	13.4	1.1	6.6	139	<0.1	0.3	0.1	23	1.99
1184678	Rock	2.42	<0.005	1.4	1.6	2.9	38	<0.1	9.0	7.6	796	2.73	7.9	<0.5	5.8	152	<0.1	0.2	0.1	27	2.26
1184729	Rock	1.40	0.005	1.3	15.5	9.4	52	<0.1	16.0	10.2	670	3.35	61.5	1.1	8.0	57	0.1	0.8	0.7	42	0.50
1184730	Rock	1.08	<0.005	1.4	15.4	9.2	52	<0.1	17.0	10.0	671	3.28	56.0	<0.5	7.3	46	<0.1	0.7	0.7	41	0.49
1184731	Rock	1.14	<0.005	1.7	14.0	7.5	51	<0.1	16.4	9.8	655	3.27	50.8	1.0	7.0	56	<0.1	0.7	0.5	38	0.79



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000357.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1184704	Rock	0.008	4	7	0.78	2663	<0.001	<20	0.31	0.004	0.28	0.3	0.24	7.5	<0.1	0.15	<1	<0.5	<0.2	
1184705	Rock	0.034	11	11	1.01	1139	<0.001	<20	0.23	0.043	0.13	0.5	0.35	10.1	<0.1	0.39	<1	<0.5	0.4	
1184706	Rock	0.027	13	11	1.03	995	0.001	<20	0.19	0.053	0.13	0.7	0.22	9.6	<0.1	0.36	<1	<0.5	0.4	
1184707	Rock	0.024	9	12	0.95	199	0.001	<20	0.18	0.066	0.09	0.7	0.26	11.9	<0.1	1.21	<1	<0.5	1.7	
1184708	Rock	0.006	8	8	0.71	150	<0.001	<20	0.24	0.047	0.12	0.6	0.32	9.8	<0.1	1.76	<1	0.5	3.3	
1184669	Rock	0.053	18	38	0.55	798	0.080	<20	1.16	0.029	0.50	0.9	0.32	6.5	0.2	<0.05	5	<0.5	0.2	
1184670	Rock Pulp	0.055	4	34	0.72	89	0.138	<20	1.49	0.083	0.13	10.3	0.05	4.7	<0.1	<0.05	5	<0.5	<0.2	
1184671	Rock	0.056	19	40	0.66	721	0.092	<20	1.21	0.028	0.61	2.1	0.27	7.0	0.2	<0.05	4	<0.5	<0.2	
1184672	Rock	0.058	17	33	0.57	622	0.071	<20	1.00	0.026	0.43	2.2	0.18	5.4	0.1	<0.05	4	<0.5	<0.2	
1184673	Rock	0.038	13	15	0.37	2437	0.021	<20	0.57	0.022	0.29	3.7	0.13	5.9	<0.1	0.09	2	<0.5	<0.2	
1184674	Rock	0.044	22	19	0.56	2134	0.081	<20	0.95	0.033	0.68	1.9	0.04	6.0	0.2	0.06	4	<0.5	<0.2	
1184675	Rock	0.035	14	14	0.22	3726	0.021	<20	0.51	0.027	0.32	2.3	0.07	6.8	<0.1	0.11	2	<0.5	<0.2	
1184676	Rock	0.032	6	7	0.20	1106	0.001	<20	0.41	0.006	0.27	0.5	0.29	11.0	<0.1	0.05	1	<0.5	<0.2	
1184677	Rock	0.040	9	8	0.37	863	0.002	<20	0.39	0.020	0.23	0.4	0.17	9.0	<0.1	<0.05	1	<0.5	<0.2	
1184678	Rock	0.037	7	10	0.42	564	0.002	<20	0.45	0.008	0.27	0.3	0.18	10.3	<0.1	<0.05	1	<0.5	<0.2	
1184729	Rock	0.060	24	42	0.71	1107	0.095	<20	1.34	0.028	0.70	1.3	0.22	7.6	0.2	<0.05	5	<0.5	<0.2	
1184730	Rock	0.057	22	43	0.71	825	0.101	<20	1.32	0.024	0.68	1.3	0.19	8.1	0.2	<0.05	5	<0.5	<0.2	
1184731	Rock	0.057	21	39	0.66	832	0.083	<20	1.22	0.024	0.63	3.3	0.19	8.2	0.2	<0.05	4	0.5	<0.2	



QUALITY CONTROL REPORT

WHI16000357.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1184652	Rock	3.15	0.019	1.9	3.2	3.9	36	<0.1	6.7	7.4	732	2.40	17.9	10.4	10.2	195	<0.1	0.6	0.3	35	1.69
REP 1184652	QC			2.2	3.3	3.8	38	<0.1	7.0	7.1	742	2.42	18.0	20.0	10.0	192	<0.1	0.7	0.3	35	1.70
1184782	Rock	3.16	0.012	3.5	22.1	12.8	34	<0.1	2.5	3.1	613	1.30	1.4	3.7	13.3	548	0.2	0.5	<0.1	14	3.86
REP 1184782	QC		0.010																		
1184802	Rock	2.35	0.071	2.1	11.3	5.0	45	<0.1	2.3	3.1	408	1.60	<0.5	24.6	8.6	83	<0.1	<0.1	<0.1	36	1.07
REP 1184802	QC			1.9	10.6	4.8	44	<0.1	2.3	3.1	401	1.56	<0.5	11.7	9.0	88	0.1	0.1	<0.1	36	1.03
1184794	Rock	2.16	0.045	3.0	5.6	3.5	38	<0.1	1.8	4.5	545	2.27	<0.5	25.5	12.0	57	<0.1	0.1	<0.1	20	1.57
REP 1184794	QC		0.055																		
1184679	Rock	2.20	0.009	2.1	2.1	5.1	22	<0.1	6.6	5.6	760	2.43	33.3	8.2	5.1	185	<0.1	0.7	0.2	21	3.32
REP 1184679	QC		0.006																		
1184688	Rock	2.63	3.501	27.1	16.4	6.9	18	1.7	6.9	5.3	461	1.76	5.5	4528.9	2.4	122	<0.1	5.1	0.7	5	1.72
REP 1184688	QC			25.8	14.9	6.6	17	1.2	6.8	5.1	443	1.66	5.1	1990.7	2.4	117	<0.1	5.0	0.6	5	1.61
1184725	Rock	1.20	0.157	2.2	9.7	24.6	31	0.6	2.1	3.6	477	2.08	7.9	227.7	6.9	138	0.1	0.7	0.2	11	1.52
REP 1184725	QC		0.165																		
1184703	Rock	2.38	0.232	2.9	5.0	3.6	34	<0.1	4.5	6.2	669	2.27	6.1	41.6	2.8	142	<0.1	0.3	0.2	12	2.53
REP 1184703	QC			2.9	5.0	3.6	35	<0.1	4.6	6.3	683	2.37	6.6	40.3	2.9	153	<0.1	0.3	0.2	12	2.49
Core Reject Duplicates																					
1184767	Rock	2.81	0.413	5.3	11.4	8.3	29	0.5	2.0	2.9	464	1.70	7.9	277.3	7.4	98	0.2	1.5	0.2	11	0.85
DUP 1184767	QC		0.366	5.7	11.3	8.7	30	0.5	2.0	3.1	471	1.75	7.6	215.5	7.8	100	0.1	1.4	0.2	11	0.86
1184792	Rock	3.81	0.022	1.3	2.3	3.4	20	<0.1	1.4	3.0	356	1.60	0.6	11.9	16.0	142	<0.1	0.2	<0.1	7	1.18
DUP 1184792	QC		0.033	1.3	2.3	3.2	20	<0.1	1.3	2.8	348	1.56	<0.5	23.6	16.2	147	<0.1	0.2	<0.1	6	1.17
1184696	Rock	2.49	0.243	3.4	4.5	3.9	33	<0.1	2.0	3.9	688	2.25	8.4	371.7	6.7	166	<0.1	0.8	<0.1	20	1.78
DUP 1184696	QC		0.153	3.5	5.4	4.1	32	<0.1	2.1	4.0	677	2.30	7.8	40.9	6.5	166	<0.1	0.8	<0.1	19	1.79
1184730	Rock	1.08	<0.005	1.4	15.4	9.2	52	<0.1	17.0	10.0	671	3.28	56.0	<0.5	7.3	46	<0.1	0.7	0.7	41	0.49
DUP 1184730	QC		<0.005	1.2	15.4	9.8	54	<0.1	17.2	9.8	673	3.34	61.0	6.2	7.9	48	0.2	0.9	0.7	42	0.51
Reference Materials																					
STD DS10	Standard			16.4	161.5	151.0	357	2.0	74.2	14.1	902	2.77	49.5	141.2	7.9	66	2.9	8.6	13.5	44	1.08
STD DS10	Standard			13.5	157.9	149.6	362	2.1	74.4	13.2	895	2.76	44.0	86.2	6.7	65	2.7	7.9	11.5	43	1.05



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 1 of 3 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000357.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1184652	Rock	0.053	21	19	0.69	1011	0.047	<20	0.66	0.056	0.47	1.2	0.07	9.8	0.3	0.12	4	<0.5	<0.2
REP 1184652	QC	0.049	21	20	0.70	1014	0.046	<20	0.65	0.055	0.47	1.3	0.06	9.8	0.3	0.12	4	<0.5	<0.2
1184782	Rock	0.031	17	10	0.20	2726	0.005	<20	0.18	0.046	0.12	4.8	0.02	2.6	<0.1	0.23	<1	<0.5	<0.2
REP 1184782	QC																		
1184802	Rock	0.030	21	11	0.34	164	0.056	<20	0.48	0.060	0.28	6.6	<0.01	1.9	0.1	0.18	3	<0.5	<0.2
REP 1184802	QC	0.029	21	11	0.34	166	0.054	<20	0.47	0.058	0.27	7.2	<0.01	1.8	0.1	0.18	3	<0.5	<0.2
1184794	Rock	0.057	31	9	0.51	333	0.108	<20	0.86	0.046	0.69	3.6	0.01	3.4	0.3	0.15	5	<0.5	<0.2
REP 1184794	QC																		
1184679	Rock	0.041	8	11	0.50	1069	<0.001	<20	0.34	0.002	0.23	0.7	0.36	8.6	<0.1	0.06	<1	<0.5	<0.2
REP 1184679	QC																		
1184688	Rock	0.017	6	9	0.55	534	<0.001	<20	0.18	0.002	0.15	3.1	0.64	5.8	<0.1	0.61	<1	<0.5	0.7
REP 1184688	QC	0.016	6	9	0.53	504	<0.001	<20	0.17	0.002	0.14	3.0	0.65	5.6	<0.1	0.57	<1	0.6	0.6
1184725	Rock	0.021	7	6	0.44	381	<0.001	<20	0.23	0.023	0.14	1.0	0.18	4.5	<0.1	0.75	<1	<0.5	0.5
REP 1184725	QC																		
1184703	Rock	0.004	4	7	0.75	747	<0.001	<20	0.31	0.003	0.28	0.3	0.24	7.1	<0.1	0.16	<1	<0.5	<0.2
REP 1184703	QC	0.004	5	7	0.76	825	<0.001	<20	0.29	0.004	0.28	0.3	0.26	7.3	<0.1	0.16	<1	<0.5	<0.2
Core Reject Duplicates																			
1184767	Rock	0.007	8	4	0.31	1618	<0.001	<20	0.24	0.007	0.15	0.9	0.11	3.5	<0.1	0.22	<1	<0.5	0.4
DUP 1184767	QC	0.007	8	4	0.31	1533	<0.001	<20	0.27	0.007	0.17	1.0	0.10	3.6	<0.1	0.24	<1	<0.5	0.3
1184792	Rock	0.026	32	8	0.26	608	0.035	<20	0.41	0.045	0.29	3.8	<0.01	1.2	0.1	0.14	2	<0.5	<0.2
DUP 1184792	QC	0.029	36	7	0.26	649	0.033	<20	0.38	0.045	0.28	3.9	<0.01	1.2	0.1	0.12	2	<0.5	<0.2
1184696	Rock	0.067	7	11	0.52	1824	0.002	<20	0.21	0.045	0.13	1.6	0.24	7.9	<0.1	0.21	<1	<0.5	<0.2
DUP 1184696	QC	0.062	7	11	0.51	1854	0.002	<20	0.22	0.050	0.13	1.6	0.26	7.8	<0.1	0.21	<1	<0.5	<0.2
1184730	Rock	0.057	22	43	0.71	825	0.101	<20	1.32	0.024	0.68	1.3	0.19	8.1	0.2	<0.05	5	<0.5	<0.2
DUP 1184730	QC	0.061	24	43	0.73	900	0.098	<20	1.36	0.026	0.70	1.4	0.19	8.1	0.2	<0.05	5	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.085	19	56	0.78	411	0.086	<20	1.04	0.071	0.34	2.9	0.27	3.2	4.8	0.29	4	2.4	4.7
STD DS10	Standard	0.072	15	56	0.74	418	0.074	<20	1.00	0.068	0.32	3.0	0.29	2.7	5.4	0.28	4	2.0	5.0



QUALITY CONTROL REPORT

WHI16000357.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS10	Standard			13.8	162.8	165.3	369	1.8	77.9	12.8	901	2.79	49.4	87.4	8.1	61	2.7	8.4	12.7	43	1.06
STD DS10	Standard			14.9	164.3	162.1	356	1.7	78.2	13.1	858	2.66	38.1	100.4	7.5	60	2.5	6.2	11.2	41	1.02
STD OREAS45EA	Standard			1.8	711.5	16.3	35	0.3	405.1	56.5	428	22.87	12.4	54.7	11.1	5	<0.1	0.4	0.3	315	0.03
STD OREAS45EA	Standard			1.7	685.4	14.9	31	0.3	378.0	50.9	412	20.62	10.2	62.9	10.6	4	<0.1	0.3	0.3	300	0.03
STD OREAS45EA	Standard			1.8	711.0	16.4	31	0.3	398.7	54.1	424	23.23	11.2	62.9	11.2	4	<0.1	0.3	0.3	316	0.03
STD OREAS45EA	Standard			1.5	678.0	16.3	29	0.2	372.6	51.2	399	20.35	8.3	54.5	11.4	3	<0.1	0.2	0.3	294	0.03
STD OXD108	Standard		0.405																		
STD OXD108	Standard		0.428																		
STD OXD108	Standard		0.401																		
STD OXD108	Standard		0.425																		
STD OXI121	Standard		1.719																		
STD OXI121	Standard		1.800																		
STD OXI121	Standard		1.768																		
STD OXI121	Standard		1.866																		
STD OXN117	Standard		7.686																		
STD OXN117	Standard		7.591																		
STD OXN117	Standard		7.719																		
STD OXN117	Standard		7.647																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	0.02	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01



QUALITY CONTROL REPORT

WHI16000357.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD DS10	Standard	0.076	16	54	0.77	421	0.077	<20	1.02	0.070	0.32	3.1	0.39	2.9	4.8	0.28	4	2.3	5.1
STD DS10	Standard	0.074	16	57	0.74	387	0.079	<20	0.98	0.067	0.32	2.7	0.28	2.9	5.0	0.28	4	2.3	4.7
STD OREAS45EA	Standard	0.036	9	870	0.10	173	0.112	<20	3.35	0.025	0.06	<0.1	<0.01	85.0	<0.1	<0.05	13	1.3	<0.2
STD OREAS45EA	Standard	0.025	7	840	0.09	149	0.091	<20	3.13	0.024	0.05	<0.1	0.01	72.4	<0.1	<0.05	12	1.0	<0.2
STD OREAS45EA	Standard	0.027	7	901	0.10	151	0.101	<20	3.29	0.025	0.06	<0.1	0.01	82.8	0.1	<0.05	13	0.7	<0.2
STD OREAS45EA	Standard	0.025	7	860	0.09	138	0.097	<20	3.07	0.019	0.05	<0.1	0.01	75.0	<0.1	<0.05	11	<0.5	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000357.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
	Prep Wash																				
ROCK-WHI	Prep Blank		<0.005	0.5	3.9	1.5	32	<0.1	0.8	4.0	407	1.64	0.6	<0.5	2.6	24	<0.1	<0.1	<0.1	22	0.51
ROCK-WHI	Prep Blank		<0.005	0.7	4.0	2.4	32	<0.1	0.8	4.1	439	1.79	0.6	<0.5	2.8	27	<0.1	<0.1	<0.1	24	0.60



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 01, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000357.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.046	5	4	0.38	62	0.083	<20	0.83	0.084	0.08	0.1	<0.01	2.6	<0.1	<0.05	3	<0.5	<0.2
ROCK-WHI	Prep Blank	0.048	6	4	0.40	74	0.096	<20	0.88	0.082	0.09	0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: October 06, 2016
Report Date: October 27, 2016
Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000358.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-10-06
P.O. Number
Number of Samples: 26

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	25	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	26	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	26	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	26	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	26	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 27, 2016

Page: 2 of 2 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000358.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1184732	Rock	1.20	0.569	1.6	7.9	6.3	33	0.1	9.7	8.6	519	2.60	19.8	670.8	8.2	87	<0.1	0.9	0.2	33	1.52
1184733	Rock	0.96	0.051	1.4	2.4	5.7	39	<0.1	5.6	7.3	585	2.31	21.1	8.4	6.4	112	<0.1	0.4	0.2	16	2.03
1184734	Rock	1.63	0.008	1.4	1.4	4.7	41	<0.1	5.4	7.6	587	2.21	21.4	3.9	6.9	101	<0.1	0.4	0.1	16	1.73
1184735	Rock	1.96	0.011	1.6	2.9	6.0	34	<0.1	5.5	6.8	636	2.18	43.1	5.0	5.8	103	<0.1	0.4	0.2	18	2.25
1184736	Rock	2.18	<0.005	1.4	1.2	5.1	28	<0.1	4.4	6.8	575	2.11	20.2	3.8	5.2	114	<0.1	0.3	0.3	14	2.00
1184737	Rock	2.09	0.013	1.4	2.7	6.9	35	<0.1	5.8	7.0	693	2.23	18.9	7.7	5.1	157	<0.1	0.4	0.2	18	2.61
1184738	Rock	2.27	0.011	1.6	2.2	6.9	38	<0.1	5.8	8.6	739	2.67	29.3	6.9	4.3	178	<0.1	0.4	0.3	22	2.84
1184739	Rock	2.25	0.008	1.6	3.1	3.6	32	<0.1	6.1	6.9	658	2.32	20.7	3.6	7.3	115	<0.1	0.4	0.2	21	1.66
1184740	Rock Pulp	0.12	2.029	67.2	2223.2	1275.2	3650	25.8	182.6	20.6	625	5.10	1185.9	1234.4	2.4	79	21.1	18.5	10.2	57	1.45
1184741	Rock	2.17	<0.005	2.3	9.9	4.1	53	<0.1	5.6	8.8	1038	3.16	21.1	1.7	6.2	123	<0.1	1.2	0.2	38	1.35
1184742	Rock	2.12	<0.005	1.8	4.2	3.3	60	<0.1	4.9	10.8	1098	4.21	5.6	1.7	7.8	175	<0.1	1.0	0.5	66	1.42
1184743	Rock	2.21	<0.005	2.5	3.6	4.1	53	<0.1	4.9	9.6	1170	3.95	21.0	2.8	6.5	169	<0.1	0.9	0.7	46	2.01
1184744	Rock	1.92	<0.005	2.3	3.2	2.8	37	<0.1	6.3	7.0	937	2.88	28.8	0.9	7.9	144	<0.1	0.7	0.2	28	1.79
1184745	Rock	1.89	<0.005	1.7	2.3	3.1	33	<0.1	6.8	6.6	814	2.28	18.2	2.9	8.3	155	<0.1	0.5	0.2	23	1.84
1184746	Rock	2.03	0.011	2.2	5.1	5.2	36	<0.1	9.0	6.6	534	2.26	28.8	8.0	8.5	106	<0.1	0.8	0.2	20	0.94
1184747	Rock	2.09	<0.005	1.7	2.5	4.5	31	<0.1	8.1	6.9	551	2.40	18.1	1.0	5.9	191	<0.1	0.5	0.2	23	1.74
1184748	Rock	1.89	<0.005	2.2	3.1	4.3	32	<0.1	11.4	8.2	618	2.57	22.8	1.3	7.7	172	<0.1	0.7	0.1	33	1.87
1184749	Rock	1.92	<0.005	2.0	2.4	2.2	34	<0.1	13.9	7.6	634	2.49	9.9	1.0	8.3	106	<0.1	0.4	0.1	38	1.46
1184750	Rock	0.79	<0.005	<0.1	1.4	1.3	15	<0.1	1.2	0.9	219	0.44	<0.5	<0.5	<0.1	45	<0.1	<0.1	<0.1	<2	18.97
1184751	Rock	2.11	<0.005	1.8	4.7	3.5	13	<0.1	2.9	2.5	351	1.04	18.0	<0.5	12.0	88	<0.1	0.7	0.2	4	0.87
1184752	Rock	2.19	<0.005	1.7	4.6	4.0	16	<0.1	1.5	2.4	490	1.25	11.3	<0.5	12.5	157	<0.1	0.5	0.1	4	1.92
1184753	Rock	2.26	<0.005	2.4	7.3	4.0	17	<0.1	2.8	2.7	411	1.45	15.3	<0.5	12.5	111	<0.1	0.6	0.3	3	1.29
1184754	Rock	1.90	<0.005	1.9	3.7	2.7	18	<0.1	1.8	2.9	477	1.40	9.9	1.0	11.4	85	<0.1	0.4	0.3	3	1.31
1184755	Rock	2.12	0.304	1.8	4.4	5.5	12	0.1	1.9	2.3	504	1.27	27.5	217.2	7.8	142	<0.1	0.6	0.4	3	1.69
1184756	Rock	3.15	2.071	2.7	12.1	6.4	15	0.4	2.1	2.8	539	1.41	32.1	751.2	7.1	126	<0.1	2.0	0.5	4	1.11
1184757	Rock	2.19	0.721	2.9	7.6	4.7	16	0.2	3.3	3.6	598	1.75	21.6	337.3	5.4	119	<0.1	1.3	0.4	5	1.47



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 27, 2016

Page: 2 of 2

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000358.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1184732	Rock	0.058	18	20	0.44	1013	0.046	<20	0.82	0.021	0.50	2.0	0.13	8.3	0.1	<0.05	4	<0.5	<0.2
1184733	Rock	0.041	9	8	0.30	522	0.002	<20	0.45	0.007	0.25	0.8	0.48	8.2	<0.1	<0.05	1	<0.5	<0.2
1184734	Rock	0.045	9	7	0.30	598	0.004	<20	0.48	0.009	0.29	0.5	0.33	8.9	0.1	<0.05	2	<0.5	<0.2
1184735	Rock	0.030	6	8	0.29	273	<0.001	<20	0.37	0.002	0.21	0.4	0.46	9.3	<0.1	<0.05	1	<0.5	<0.2
1184736	Rock	0.032	6	6	0.44	257	<0.001	<20	0.35	0.003	0.19	0.4	0.32	8.7	<0.1	0.06	<1	<0.5	<0.2
1184737	Rock	0.034	5	8	0.52	1176	<0.001	<20	0.36	0.003	0.21	0.4	0.33	10.1	<0.1	0.08	1	<0.5	<0.2
1184738	Rock	0.029	6	7	0.43	697	<0.001	<20	0.42	0.006	0.23	0.4	0.28	10.7	<0.1	0.12	1	<0.5	<0.2
1184739	Rock	0.042	10	9	0.27	638	0.002	<20	0.42	0.020	0.24	0.4	0.11	9.1	<0.1	0.08	2	<0.5	<0.2
1184740	Rock Pulp	0.071	11	46	0.85	236	0.090	<20	1.48	0.080	0.19	8.8	0.75	4.8	1.4	1.48	6	4.4	0.6
1184741	Rock	0.048	12	9	0.31	1689	0.007	<20	0.46	0.029	0.28	0.6	0.08	10.2	0.1	0.14	2	<0.5	<0.2
1184742	Rock	0.065	20	10	0.64	1382	0.056	<20	0.96	0.031	0.67	0.4	0.04	14.0	0.2	0.16	5	0.6	<0.2
1184743	Rock	0.055	11	8	0.46	1288	0.010	<20	0.62	0.022	0.39	0.4	0.15	13.2	0.2	0.12	3	0.6	<0.2
1184744	Rock	0.043	13	12	0.43	1116	0.004	<20	0.41	0.025	0.25	0.6	0.14	10.0	0.1	0.06	2	<0.5	<0.2
1184745	Rock	0.047	16	13	0.38	1218	0.004	<20	0.42	0.024	0.25	0.7	0.17	8.7	<0.1	0.09	2	<0.5	<0.2
1184746	Rock	0.062	22	15	0.19	1168	0.002	<20	0.35	0.030	0.19	0.5	0.15	9.0	<0.1	0.09	2	0.6	<0.2
1184747	Rock	0.056	9	11	0.41	2102	0.001	<20	0.36	0.019	0.22	0.6	0.15	9.8	<0.1	0.16	1	<0.5	<0.2
1184748	Rock	0.058	17	23	0.53	2865	0.037	<20	0.76	0.023	0.54	0.6	0.04	9.0	0.2	0.15	3	<0.5	<0.2
1184749	Rock	0.062	21	31	0.67	965	0.081	<20	0.97	0.025	0.77	0.6	0.03	8.6	0.2	0.09	5	<0.5	<0.2
1184750	Rock	0.016	<1	<1	11.80	33	<0.001	<20	0.04	<0.001	0.02	<0.1	<0.01	0.4	<0.1	<0.05	<1	<0.5	<0.2
1184751	Rock	0.014	28	8	0.12	995	0.005	<20	0.26	0.033	0.16	3.0	0.09	5.2	<0.1	0.17	2	<0.5	<0.2
1184752	Rock	0.014	28	7	0.13	878	0.002	<20	0.22	0.028	0.14	2.7	0.10	4.8	<0.1	0.21	1	<0.5	<0.2
1184753	Rock	0.012	33	10	0.08	787	0.003	<20	0.24	0.029	0.15	2.9	0.16	5.8	<0.1	0.25	2	0.5	<0.2
1184754	Rock	0.013	29	7	0.11	587	0.004	<20	0.26	0.027	0.17	2.4	0.17	5.9	<0.1	0.29	2	0.5	<0.2
1184755	Rock	0.009	20	5	0.08	649	<0.001	<20	0.23	0.015	0.19	1.0	0.56	4.5	<0.1	0.19	1	<0.5	<0.2
1184756	Rock	0.010	20	6	0.19	1551	<0.001	<20	0.23	0.005	0.19	2.0	1.10	5.0	<0.1	0.30	<1	<0.5	0.3
1184757	Rock	0.008	13	7	0.31	1491	<0.001	<20	0.26	0.003	0.22	1.7	0.53	5.6	<0.1	0.29	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 27, 2016

Page: 1 of 1

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000358.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1184751	Rock	2.11	<0.005	1.8	4.7	3.5	13	<0.1	2.9	2.5	351	1.04	18.0	<0.5	12.0	88	<0.1	0.7	0.2	4	0.87
REP 1184751	QC			1.7	4.6	3.3	13	<0.1	2.8	2.4	342	1.00	17.6	<0.5	11.0	85	<0.1	0.7	0.1	4	0.87
Reference Materials																					
STD DS10	Standard			14.5	154.1	157.8	366	2.0	78.0	13.1	847	2.72	45.0	53.7	7.1	67	2.7	8.6	13.2	42	1.05
STD OREAS45EA	Standard			1.8	703.2	15.6	31	0.3	392.0	51.0	414	21.29	11.7	51.7	10.0	4	<0.1	0.3	0.3	300	0.03
STD OXD108	Standard	0.421																			
STD OXD108	Standard	0.422																			
STD OXI121	Standard	1.829																			
STD OXI121	Standard	1.775																			
STD OXN117	Standard	7.722																			
STD OXN117	Standard	7.642																			
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected		0.414																			
STD OXN117 Expected		7.679																			
STD OXI121 Expected		1.834																			
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
Prep Wash																					
ROCK-WHI	Prep Blank	<0.005	0.7	2.4	1.8	30	<0.1	0.6	3.9	418	1.69	<0.5	<0.5	2.2	26	<0.1	<0.1	<0.1	22	0.58	
ROCK-WHI	Prep Blank	<0.005	0.5	3.9	1.6	30	<0.1	0.6	4.0	421	1.71	0.7	<0.5	2.3	21	<0.1	<0.1	<0.1	23	0.55	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: October 27, 2016

Page: 1 of 1

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000358.1

Method		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1184751	Rock	0.014	28	8	0.12	995	0.005	<20	0.26	0.033	0.16	3.0	0.09	5.2	<0.1	0.17	2	<0.5	<0.2
REP 1184751	QC	0.014	28	8	0.11	951	0.005	<20	0.26	0.032	0.16	2.7	0.09	5.1	<0.1	0.17	1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.080	18	55	0.76	398	0.081	<20	1.04	0.067	0.33	3.9	0.28	3.1	5.4	0.29	5	2.2	5.2
STD OREAS45EA	Standard	0.030	7	844	0.09	138	0.094	<20	3.25	0.018	0.06	<0.1	0.01	74.5	<0.1	<0.05	12	1.5	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	2	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.043	5	3	0.38	73	0.083	<20	0.97	0.135	0.12	0.1	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.043	5	4	0.39	56	0.084	<20	0.89	0.105	0.10	0.1	<0.01	2.5	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: October 17, 2016
Report Date: November 03, 2016
Page: 1 of 5

CERTIFICATE OF ANALYSIS

WHI16000366.1

CLIENT JOB INFORMATION

Project: QV
Shipment ID: QVV2016-10-14
P.O. Number
Number of Samples: 113

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	109	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	113	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	113	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	113	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	113	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 2 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419601	Rock	1.03	0.029	1.4	18.3	5.0	42	<0.1	3.5	4.8	561	2.93	4.8	31.4	10.0	37	<0.1	0.4	0.5	19	0.35
1419602	Rock	1.85	0.014	1.6	26.8	7.6	46	<0.1	2.6	3.8	485	2.73	4.8	18.3	13.3	43	<0.1	0.4	0.4	13	0.19
1419603	Rock	1.81	0.022	1.4	17.4	9.1	30	<0.1	3.1	3.3	374	2.38	18.7	24.0	10.5	25	<0.1	0.3	0.5	11	0.16
1419604	Rock	2.38	0.007	1.4	12.1	5.3	34	<0.1	4.8	4.0	456	2.57	6.4	7.7	10.8	37	0.2	0.4	0.3	16	0.45
1419605	Rock	2.09	0.026	1.9	11.1	24.5	18	<0.1	2.3	2.1	360	1.70	13.4	19.5	13.0	31	<0.1	0.3	0.6	5	0.06
1419606	Rock	1.00	<0.005	1.3	12.7	12.3	10	<0.1	1.9	1.3	194	1.01	7.5	2.4	13.5	24	<0.1	0.3	0.3	3	0.06
1419607	Rock	0.83	<0.005	1.1	13.5	10.0	15	<0.1	1.5	1.2	195	1.06	13.6	3.0	10.1	26	<0.1	0.3	0.2	3	0.06
1419608	Rock	1.67	0.011	1.2	11.2	5.7	14	<0.1	2.2	1.4	229	1.13	13.4	50.8	10.1	24	<0.1	0.3	0.1	4	0.05
1419609	Rock	1.47	0.051	1.9	13.0	11.1	34	<0.1	1.1	2.8	429	1.77	18.8	43.9	6.9	39	0.1	0.5	0.2	4	0.10
1419610	Rock Pulp	0.09	0.734	4.3	36.8	5.7	50	0.2	24.1	9.3	410	2.56	6.5	394.7	1.0	43	0.2	0.8	0.1	60	0.84
1419611	Rock	1.54	0.068	2.1	10.1	19.8	35	<0.1	1.4	2.6	456	1.63	37.7	23.8	8.1	63	0.1	0.5	<0.1	7	0.11
1419612	Rock	1.31	0.018	1.5	11.1	12.2	24	<0.1	1.7	1.6	478	1.51	49.8	20.8	11.8	29	<0.1	0.4	<0.1	7	0.09
1419613	Rock	1.66	0.009	1.1	11.3	10.5	15	<0.1	1.9	1.3	263	1.11	30.6	11.6	11.4	42	<0.1	0.2	0.1	5	0.09
1419614	Rock	1.81	<0.005	0.9	7.1	21.6	15	<0.1	0.9	2.0	308	1.16	46.5	8.2	6.5	75	<0.1	0.3	0.1	7	0.09
1419615	Rock	2.12	0.009	1.7	5.5	24.0	27	<0.1	1.2	2.0	325	1.24	55.3	11.5	9.4	69	<0.1	0.4	<0.1	10	0.16
1419616	Rock	2.11	<0.005	1.7	15.6	17.2	24	<0.1	1.2	2.3	305	1.56	37.1	1.2	9.4	58	0.1	0.5	0.1	4	0.65
1419617	Rock	1.97	0.015	1.5	15.0	8.7	29	<0.1	1.8	2.8	390	1.96	26.4	12.8	9.5	74	0.1	0.5	0.2	6	0.13
1419618	Rock	1.75	4.703	2.3	8.8	12.1	23	0.2	2.0	3.1	506	1.65	60.4	980.9	8.3	70	0.1	0.5	0.1	9	0.10
1419619	Rock	1.90	2.198	5.6	7.5	14.4	18	0.5	3.5	2.9	530	1.80	47.3	1125.6	8.8	52	<0.1	0.3	0.2	9	0.09
1419620	Rock	0.48	<0.005	0.1	2.6	1.2	15	<0.1	1.2	0.7	220	0.47	0.8	0.6	<0.1	50	<0.1	<0.1	<0.1	5	18.72
1419621	Rock	2.36	1.868	7.4	11.5	15.0	24	0.7	1.8	4.1	419	2.08	23.8	2057.5	10.1	34	0.1	0.3	0.5	5	0.16
1419622	Rock	2.12	0.309	3.2	6.6	14.2	21	0.2	1.6	2.7	486	1.44	26.6	240.7	9.8	61	<0.1	0.3	<0.1	8	1.08
1419623	Rock	1.72	0.084	1.9	17.1	18.7	19	0.1	0.9	3.0	259	1.81	24.0	35.3	5.6	61	<0.1	0.3	0.4	4	0.20
1419624	Rock	1.70	2.896	3.6	13.8	15.6	22	0.2	1.9	2.9	403	1.88	37.1	224.2	8.8	72	0.1	0.3	0.2	9	1.14
1419625	Rock	1.69	0.167	4.1	11.9	16.8	26	0.1	3.2	3.8	1047	2.10	28.2	172.1	7.0	86	0.2	0.4	0.3	13	3.35
1419626	Rock	0.98	0.460	4.6	14.8	13.3	23	<0.1	3.1	3.8	771	1.83	38.0	28.9	7.3	60	<0.1	0.4	0.5	7	0.51
1419627	Rock	1.47	0.022	3.5	18.5	16.1	34	<0.1	6.5	7.2	489	2.29	24.8	15.4	8.5	66	<0.1	0.4	0.5	14	1.94
1419628	Rock	1.72	0.260	2.6	10.0	15.0	21	0.1	2.9	2.9	542	1.57	18.8	229.1	9.2	90	<0.1	0.3	0.2	6	2.48
1419629	Rock	2.34	0.060	3.2	7.5	18.9	23	<0.1	1.5	3.0	619	1.80	29.3	82.0	8.9	63	<0.1	0.2	0.4	4	1.14
1419630	Rock	2.54	0.053	3.8	7.3	19.7	25	<0.1	2.3	3.8	618	2.01	29.5	39.9	8.5	66	0.1	0.2	0.5	4	1.04



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 2 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419601	Rock	0.071	29	6	0.28	842	0.052	<20	0.87	0.028	0.44	0.3	0.15	7.1	0.2	<0.05	4	<0.5	0.3
1419602	Rock	0.048	32	6	0.18	1075	0.041	<20	0.69	0.029	0.38	0.4	0.16	7.1	0.2	<0.05	4	<0.5	<0.2
1419603	Rock	0.044	20	6	0.14	462	0.012	<20	0.58	0.018	0.31	0.4	0.28	6.4	0.1	<0.05	3	<0.5	<0.2
1419604	Rock	0.039	20	8	0.16	897	0.012	<20	0.54	0.015	0.29	0.5	0.24	6.6	0.1	<0.05	3	<0.5	<0.2
1419605	Rock	0.003	17	5	0.05	1008	<0.001	<20	0.28	0.004	0.16	0.9	0.19	2.1	<0.1	<0.05	1	<0.5	<0.2
1419606	Rock	0.003	19	7	0.04	711	<0.001	<20	0.30	0.002	0.16	0.8	0.11	1.8	<0.1	<0.05	1	<0.5	<0.2
1419607	Rock	0.003	15	5	0.05	592	<0.001	<20	0.29	0.005	0.13	0.6	0.13	2.8	<0.1	<0.05	<1	<0.5	<0.2
1419608	Rock	0.004	16	5	0.04	272	<0.001	<20	0.31	0.015	0.11	0.3	0.11	2.3	<0.1	<0.05	<1	<0.5	<0.2
1419609	Rock	0.009	16	3	0.07	1151	<0.001	<20	0.38	0.006	0.19	0.3	0.17	3.4	<0.1	<0.05	1	<0.5	<0.2
1419610	Rock Pulp	0.058	5	36	0.74	94	0.133	<20	1.54	0.086	0.14	10.6	0.05	4.8	<0.1	<0.05	5	<0.5	<0.2
1419611	Rock	0.009	20	4	0.08	2843	<0.001	<20	0.44	0.005	0.18	0.4	0.27	2.9	<0.1	0.07	2	<0.5	<0.2
1419612	Rock	0.007	21	4	0.06	752	<0.001	<20	0.38	0.009	0.15	0.4	0.17	2.8	<0.1	<0.05	1	<0.5	<0.2
1419613	Rock	0.008	21	5	0.06	1029	<0.001	<20	0.44	0.012	0.18	0.3	0.22	3.4	<0.1	<0.05	2	<0.5	<0.2
1419614	Rock	0.008	14	3	0.06	2845	<0.001	<20	0.39	0.012	0.16	0.5	0.14	3.1	<0.1	0.07	1	<0.5	<0.2
1419615	Rock	0.017	28	3	0.08	2317	<0.001	<20	0.52	0.005	0.20	0.2	0.26	3.5	<0.1	0.05	2	<0.5	<0.2
1419616	Rock	0.017	19	3	0.05	1269	<0.001	<20	0.31	0.002	0.18	0.3	0.33	3.0	<0.1	<0.05	<1	<0.5	<0.2
1419617	Rock	0.022	18	4	0.04	2143	<0.001	<20	0.34	0.016	0.18	0.3	0.27	3.5	<0.1	0.05	1	<0.5	<0.2
1419618	Rock	0.011	23	5	0.04	2059	<0.001	<20	0.30	0.005	0.15	0.4	0.35	3.7	<0.1	<0.05	1	<0.5	0.3
1419619	Rock	0.015	25	9	0.04	1481	<0.001	<20	0.36	0.005	0.17	0.5	0.36	3.0	<0.1	<0.05	1	<0.5	0.4
1419620	Rock	0.014	<1	<1	11.92	26	<0.001	<20	0.02	<0.001	0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1419621	Rock	0.030	20	4	0.06	357	<0.001	<20	0.41	0.007	0.20	0.3	0.19	3.1	<0.1	<0.05	1	<0.5	0.6
1419622	Rock	0.015	20	3	0.05	1375	<0.001	<20	0.35	0.003	0.17	0.3	0.15	3.3	<0.1	<0.05	1	<0.5	<0.2
1419623	Rock	0.020	9	3	0.05	975	<0.001	<20	0.32	0.002	0.17	0.2	0.16	3.3	<0.1	<0.05	<1	<0.5	<0.2
1419624	Rock	0.013	16	4	0.04	1521	<0.001	<20	0.34	0.004	0.20	0.3	0.25	4.3	<0.1	<0.05	<1	<0.5	0.3
1419625	Rock	0.024	12	5	0.07	1189	<0.001	<20	0.31	0.005	0.18	0.4	0.18	5.6	<0.1	<0.05	<1	<0.5	<0.2
1419626	Rock	0.018	12	6	0.05	717	<0.001	<20	0.37	0.003	0.19	0.5	0.18	3.8	<0.1	<0.05	1	<0.5	<0.2
1419627	Rock	0.038	17	10	0.08	630	<0.001	<20	0.40	0.005	0.19	0.2	0.13	6.9	<0.1	<0.05	1	<0.5	<0.2
1419628	Rock	0.023	16	5	0.07	1579	<0.001	<20	0.36	0.008	0.18	0.4	0.09	3.4	<0.1	<0.05	1	<0.5	<0.2
1419629	Rock	0.009	13	4	0.06	1006	<0.001	<20	0.35	0.003	0.17	0.6	0.07	2.7	<0.1	<0.05	1	<0.5	<0.2
1419630	Rock	0.011	14	5	0.06	1208	<0.001	<20	0.41	0.003	0.20	0.6	0.09	2.9	0.1	<0.05	1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 3 of 5 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1419631	Rock	1.19	0.051	1.6	9.9	15.1	14	0.1	0.9	2.8	133	1.10	9.3	69.8	3.9	52	<0.1	0.2	0.5	<2	0.16
1419632	Rock	1.25	0.170	3.2	7.7	11.4	17	0.2	1.8	3.5	356	2.04	11.8	135.0	8.8	54	<0.1	0.2	0.3	7	0.14
1419633	Rock	1.41	0.113	2.3	10.8	11.4	30	0.1	1.1	3.2	296	1.97	18.4	82.9	11.2	46	<0.1	0.3	0.2	9	0.15
1419634	Rock	0.77	0.140	3.0	11.0	14.5	21	0.1	1.8	3.3	363	1.80	11.4	63.1	8.5	59	0.1	0.2	0.3	6	0.12
1419635	Rock	1.59	0.080	2.6	10.6	15.3	21	<0.1	1.3	2.6	386	1.69	9.6	55.4	9.0	61	<0.1	0.2	0.4	5	0.12
1419636	Rock	1.59	0.046	2.4	13.9	21.1	30	0.1	1.2	2.4	169	1.65	15.8	37.7	9.3	50	0.2	0.3	0.4	4	0.11
1419637	Rock	1.54	0.047	2.5	12.5	19.7	25	0.2	1.9	2.2	269	1.26	12.5	36.3	6.9	70	0.4	0.3	0.5	2	0.59
1419638	Rock	2.43	0.143	2.3	20.7	11.5	15	0.4	1.4	2.3	218	1.63	4.8	105.8	10.1	74	<0.1	1.4	2.3	3	0.50
1419639	Rock	1.95	0.029	2.9	10.6	11.4	22	0.1	1.7	3.1	274	1.90	13.7	29.5	7.8	63	<0.1	0.4	0.6	3	0.67
1419640	Rock Pulp	0.13	2.369	67.6	2139.7	1242.6	3570	24.8	176.8	18.9	599	5.09	1175.1	2195.2	2.5	78	22.1	13.2	9.7	54	1.45
1419641	Rock	1.75	0.009	2.8	10.5	41.6	24	0.1	1.5	3.5	463	1.84	4.7	18.2	7.2	80	<0.1	0.5	0.7	4	1.12
1419642	Rock	2.50	1.012	5.4	16.2	8.7	15	0.8	1.3	2.6	232	1.74	6.3	3969.2	9.4	46	<0.1	1.7	0.8	8	0.38
1419643	Rock	2.51	1.282	3.7	11.7	8.0	16	0.4	1.9	3.4	343	1.89	4.4	1107.5	10.8	58	<0.1	1.1	0.4	8	0.92
1419644	Rock	2.40	0.425	10.5	10.8	10.5	16	0.6	2.2	3.8	498	2.03	31.9	672.5	9.5	85	<0.1	0.7	0.5	10	1.09
1419645	Rock	1.98	0.340	3.2	10.0	13.2	18	0.2	1.7	3.4	454	1.92	15.2	300.6	10.2	85	<0.1	0.4	0.4	8	1.49
1419646	Rock	2.41	0.722	6.4	11.7	12.6	18	0.4	2.6	3.5	441	1.89	7.6	513.0	7.7	93	0.1	0.5	0.2	11	1.54
1419647	Rock	3.02	0.356	5.9	8.5	7.9	21	0.1	2.8	4.2	456	1.84	13.2	197.4	10.7	98	<0.1	0.3	<0.1	12	1.08
1419648	Rock	2.83	1.398	9.9	11.2	7.6	14	0.4	2.1	2.8	315	1.53	14.2	878.5	12.9	72	<0.1	0.6	0.1	9	0.29
1419649	Rock	1.82	2.071	26.1	17.2	21.0	16	2.6	1.8	3.5	284	1.86	22.8	2255.2	11.1	78	0.2	1.0	0.7	8	0.64
1419650	Rock	0.45	0.102	<0.1	21.2	1.4	16	0.2	1.7	0.7	213	0.41	<0.5	38.1	<0.1	50	<0.1	<0.1	1.4	<2	18.29
1419651	Rock	1.49	0.735	23.8	15.0	9.1	27	0.6	2.8	5.8	736	2.68	20.0	579.0	8.9	91	0.2	1.2	0.2	14	1.72
1419652	Rock	2.04	0.624	26.8	11.1	8.9	35	0.8	3.5	6.4	661	2.70	38.0	746.4	10.7	82	0.2	1.3	0.2	16	1.23
1419653	Rock	2.27	0.284	15.0	20.1	11.1	31	0.3	5.0	4.4	475	2.02	12.9	308.2	13.0	90	0.2	1.2	0.2	12	1.33
1419654	Rock	5.92	0.624	13.0	23.3	21.7	59	1.1	2.1	5.3	504	2.70	8.8	589.1	11.5	82	0.4	1.2	0.2	13	1.07
1419655	Rock	5.37	0.891	15.9	20.8	10.2	32	1.7	2.2	4.7	421	2.37	7.6	842.2	11.7	77	0.1	1.8	0.1	12	1.04
1419656	Rock	2.40	0.349	14.8	9.9	6.3	21	0.3	2.7	3.0	446	1.76	9.1	247.2	9.8	115	0.1	0.9	<0.1	9	1.46
1419657	Rock	1.99	0.217	13.4	20.5	7.7	46	0.2	2.3	5.3	540	2.48	8.7	162.0	14.1	112	0.1	1.8	<0.1	19	1.47
1419658	Rock	1.91	1.492	13.3	14.7	45.0	34	5.5	1.8	4.6	548	2.31	7.8	2089.7	12.0	80	0.1	2.0	1.1	15	1.14
1419659	Rock	1.65	0.489	17.1	16.3	11.5	35	1.3	2.8	5.9	643	2.47	11.8	2937.1	9.4	125	0.1	2.2	0.2	12	1.64
1419660	Rock	1.82	0.383	16.5	13.0	12.4	34	0.7	1.8	4.7	593	2.34	12.3	238.2	9.1	104	0.1	1.8	0.3	10	1.37



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 3 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419631	Rock	0.012	8	2	0.04	1100	<0.001	<20	0.30	0.002	0.17	0.3	0.10	2.5	<0.1	<0.05	<1	<0.5	<0.2
1419632	Rock	0.026	18	5	0.04	1241	<0.001	<20	0.31	0.018	0.14	0.5	0.09	3.2	<0.1	<0.05	<1	<0.5	0.3
1419633	Rock	0.033	20	3	0.05	835	<0.001	<20	0.31	0.018	0.13	0.3	0.11	4.0	<0.1	<0.05	<1	<0.5	<0.2
1419634	Rock	0.016	15	4	0.04	1849	<0.001	<20	0.30	0.009	0.14	0.4	0.09	2.9	<0.1	<0.05	1	<0.5	0.2
1419635	Rock	0.020	17	3	0.04	1698	<0.001	<20	0.31	0.009	0.15	0.3	0.08	2.8	<0.1	<0.05	1	<0.5	0.2
1419636	Rock	0.014	14	4	0.03	997	<0.001	<20	0.30	0.006	0.14	0.3	0.12	2.9	<0.1	<0.05	<1	1.0	<0.2
1419637	Rock	0.007	9	4	0.03	1149	<0.001	<20	0.30	0.003	0.17	0.4	0.20	2.5	<0.1	<0.05	<1	<0.5	<0.2
1419638	Rock	0.007	17	3	0.03	1263	<0.001	<20	0.25	0.016	0.13	0.3	0.34	2.7	<0.1	<0.05	<1	0.9	0.5
1419639	Rock	0.005	12	3	0.03	678	<0.001	<20	0.29	0.006	0.17	0.3	0.22	2.7	<0.1	<0.05	<1	<0.5	0.2
1419640	Rock Pulp	0.061	11	44	0.84	158	0.094	<20	1.48	0.081	0.18	7.6	0.73	4.7	1.3	1.46	6	3.7	0.5
1419641	Rock	0.008	10	4	0.04	708	<0.001	<20	0.31	0.010	0.17	0.2	0.18	3.4	<0.1	<0.05	1	<0.5	<0.2
1419642	Rock	0.008	23	5	0.02	560	<0.001	<20	0.22	0.015	0.12	0.7	0.31	3.8	<0.1	0.12	<1	<0.5	0.4
1419643	Rock	0.016	24	5	0.03	627	<0.001	<20	0.23	0.017	0.14	1.1	0.37	3.8	<0.1	0.18	<1	<0.5	0.3
1419644	Rock	0.030	25	5	0.03	1174	<0.001	<20	0.31	0.019	0.16	0.6	0.29	4.6	<0.1	<0.05	1	<0.5	0.7
1419645	Rock	0.018	15	6	0.04	995	<0.001	<20	0.32	0.004	0.21	0.6	0.50	3.5	<0.1	0.07	1	<0.5	<0.2
1419646	Rock	0.011	16	4	0.03	1364	<0.001	<20	0.31	0.009	0.18	0.3	0.39	3.9	<0.1	<0.05	<1	<0.5	0.3
1419647	Rock	0.032	22	6	0.03	1818	<0.001	<20	0.26	0.020	0.14	0.4	0.12	3.9	<0.1	<0.05	<1	<0.5	<0.2
1419648	Rock	0.017	32	5	0.03	1454	<0.001	<20	0.25	0.022	0.12	0.4	0.19	3.9	<0.1	<0.05	<1	<0.5	0.2
1419649	Rock	0.034	24	4	0.02	1150	<0.001	<20	0.24	0.019	0.12	0.7	0.45	3.6	<0.1	0.07	<1	<0.5	1.7
1419650	Rock	0.014	<1	<1	11.00	30	<0.001	<20	0.07	0.001	0.05	<0.1	<0.01	0.6	<0.1	<0.05	<1	<0.5	<0.2
1419651	Rock	0.059	18	6	0.06	535	0.001	<20	0.31	0.020	0.21	1.1	0.59	4.3	<0.1	0.14	1	<0.5	0.7
1419652	Rock	0.054	24	8	0.05	637	0.003	<20	0.29	0.022	0.14	1.2	0.28	4.8	<0.1	0.09	1	<0.5	0.7
1419653	Rock	0.039	26	13	0.15	695	0.006	<20	0.33	0.028	0.21	2.1	0.34	3.7	<0.1	0.18	2	<0.5	0.3
1419654	Rock	0.054	32	6	0.22	599	0.032	<20	0.44	0.034	0.32	1.8	1.13	4.3	0.1	0.54	3	<0.5	1.4
1419655	Rock	0.047	27	6	0.10	613	0.022	<20	0.39	0.033	0.26	1.5	0.89	3.3	<0.1	0.36	2	<0.5	1.4
1419656	Rock	0.026	18	8	0.08	1177	0.001	<20	0.26	0.026	0.17	1.1	0.31	3.3	<0.1	0.12	<1	<0.5	0.3
1419657	Rock	0.058	33	9	0.20	592	0.026	<20	0.44	0.029	0.32	1.4	0.26	4.0	0.1	0.22	3	<0.5	<0.2
1419658	Rock	0.046	31	6	0.10	493	0.013	<20	0.33	0.034	0.22	1.6	0.60	3.4	0.2	0.24	2	<0.5	3.2
1419659	Rock	0.057	23	8	0.10	1266	0.007	<20	0.38	0.028	0.26	0.8	0.53	4.0	0.1	0.18	2	<0.5	0.6
1419660	Rock	0.045	21	6	0.08	863	0.005	<20	0.31	0.022	0.22	0.9	0.40	3.4	<0.1	0.15	1	<0.5	0.4



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 4 of 5 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit	MDL	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1419661	Rock	2.68	1.586	57.5	32.4	15.5	22	2.6	2.6	5.4	395	2.01	8.2	1019.5	7.3	85	0.2	4.5	0.6	6	1.24
1419662	Rock	3.13	6.370	254.5	37.8	37.9	16	4.6	8.7	7.2	286	1.94	9.6	5718.7	2.8	78	0.8	9.7	1.5	2	0.58
1419663	Rock	2.71	3.233	90.6	109.1	14.8	28	2.9	5.8	6.1	609	1.92	14.5	3101.6	5.8	125	0.4	19.2	0.6	7	1.72
1419664	Rock	2.00	8.019	202.4	24.3	34.4	16	6.0	8.5	6.7	366	2.19	7.9	9738.1	4.2	63	0.6	5.4	1.8	2	0.56
1419665	Rock	2.79	5.216	110.0	23.4	11.9	19	4.3	5.8	5.6	523	2.25	5.4	9147.5	6.7	89	0.4	4.6	0.6	3	1.18
1419666	Rock	1.99	6.362	279.4	49.7	25.6	22	6.3	6.0	5.8	488	2.35	7.6	8261.2	5.6	79	0.9	11.4	1.2	<2	0.93
1419667	Rock	1.72	5.791	74.1	26.0	10.6	17	3.8	7.2	5.3	391	2.06	6.2	4256.6	8.2	68	0.4	5.2	0.6	<2	0.69
1419668	Rock	2.40	5.675	106.3	16.4	12.0	16	2.7	4.6	4.5	469	2.04	11.0	4002.7	8.0	105	0.4	3.1	0.5	2	0.58
1419669	Rock	2.34	3.536	132.8	7.5	13.0	12	2.0	4.5	3.6	457	1.80	6.9	3126.2	13.9	78	0.3	1.2	0.7	3	0.89
1419670	Rock Pulp	0.12	0.868	4.5	35.5	5.3	54	0.2	25.1	9.1	390	2.53	6.4	403.8	0.9	43	0.2	0.7	0.1	57	0.82
1419671	Rock	2.33	0.758	28.6	4.9	4.8	17	0.6	3.0	3.3	791	1.89	4.2	1093.8	13.6	128	0.2	0.7	<0.1	7	1.61
1419672	Rock	2.16	1.185	10.6	4.5	5.1	13	0.3	3.0	4.5	671	2.08	3.9	573.1	14.4	107	0.1	0.4	0.1	7	1.46
1419673	Rock	1.96	0.640	11.7	4.0	5.8	11	0.3	2.5	5.2	591	1.93	3.6	844.2	15.8	89	0.1	0.4	0.1	8	1.14
1419674	Rock	3.11	3.011	41.1	7.0	10.3	11	2.8	4.0	3.2	515	1.82	8.1	18116.8	14.6	93	0.2	1.1	0.4	6	1.05
1419675	Rock	2.14	4.728	25.5	18.5	12.6	13	1.5	5.6	6.6	540	2.29	3.9	3217.7	13.9	89	0.1	2.8	0.5	3	1.27
1419676	Rock	2.28	1.137	13.7	3.9	5.0	15	0.3	2.1	3.1	604	1.75	4.3	848.4	20.5	124	0.1	0.4	0.1	6	1.53
1419677	Rock	1.30	0.339	6.8	4.7	5.3	17	0.2	5.2	2.2	843	1.64	4.3	273.3	18.0	153	0.2	0.7	<0.1	9	1.98
1419678	Rock	0.94	0.211	6.0	5.2	7.6	11	0.1	2.5	1.7	497	1.54	14.0	115.4	16.1	116	0.1	0.6	<0.1	8	1.02
1419679	Rock	1.71	0.145	5.6	5.1	5.2	10	<0.1	3.1	2.0	446	1.39	12.8	103.5	17.1	123	0.1	0.5	<0.1	7	1.02
1419680	Rock	0.58	<0.005	<0.1	1.3	1.1	14	<0.1	1.5	0.6	200	0.39	<0.5	<0.5	<0.1	45	<0.1	<0.1	<0.1	<2	19.39
1456550	Rock	0.75	<0.005	0.1	1.3	1.4	14	<0.1	1.9	0.6	217	0.43	<0.5	<0.5	<0.1	49	<0.1	<0.1	<0.1	<2	19.66
1456551	Rock	2.07	0.035	4.9	13.2	10.1	30	<0.1	18.9	5.0	618	2.04	18.9	28.6	15.3	101	0.1	1.3	0.2	17	0.54
1456552	Rock	2.06	0.183	10.2	11.7	6.1	39	0.1	30.6	10.9	676	3.09	24.6	59.0	9.2	122	0.2	1.7	0.1	35	0.97
1456553	Rock	1.32	0.080	16.9	12.2	7.8	52	<0.1	36.2	17.0	940	4.01	102.4	81.2	15.9	192	0.2	2.0	0.2	48	1.82
1456554	Rock	1.10	0.153	20.8	14.7	10.8	71	<0.1	60.4	23.2	1153	5.10	224.0	35.6	16.9	168	0.3	3.4	<0.1	62	0.31
1456555	Rock	2.55	0.177	16.5	20.5	9.4	43	0.1	63.7	16.0	1084	3.06	165.3	119.0	12.5	198	0.2	3.5	0.1	27	0.18
1456556	Rock	1.37	0.116	10.3	40.9	8.3	37	0.1	44.0	11.9	564	2.62	72.9	90.0	21.4	123	0.2	5.4	0.2	19	0.24
1456557	Rock	2.27	0.175	12.1	24.5	9.0	34	0.2	47.6	10.9	905	2.48	144.0	177.1	7.6	109	0.3	4.2	0.1	22	1.20
1456558	Rock	2.59	0.899	11.7	20.2	11.4	30	0.9	45.6	13.1	883	2.10	131.0	3396.1	14.3	142	0.2	4.2	<0.1	17	1.24
1456559	Rock	2.54	0.018	11.7	3.8	5.9	46	<0.1	45.4	15.9	590	3.27	38.4	18.3	10.6	204	0.2	0.7	<0.1	28	6.76



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 4 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1419661	Rock	0.031	16	6	0.20	702	0.002	<20	0.26	0.023	0.17	2.7	0.92	2.7	<0.1	0.47	<1	0.5	1.8
1419662	Rock	0.015	5	7	0.06	374	<0.001	<20	0.16	0.003	0.12	4.6	0.70	2.2	0.1	0.78	<1	1.3	3.0
1419663	Rock	0.044	10	7	0.25	731	<0.001	<20	0.26	0.004	0.24	1.4	1.49	4.9	0.1	0.51	<1	<0.5	1.0
1419664	Rock	0.022	10	7	0.08	242	<0.001	<20	0.18	0.003	0.15	3.2	0.69	2.8	<0.1	0.85	<1	0.6	2.8
1419665	Rock	0.038	12	6	0.14	246	<0.001	<20	0.22	0.003	0.17	1.4	0.97	4.0	<0.1	0.89	<1	0.7	1.5
1419666	Rock	0.038	9	6	0.25	165	<0.001	<20	0.18	0.003	0.14	2.6	1.03	3.1	<0.1	1.37	<1	1.9	2.2
1419667	Rock	0.031	13	8	0.15	197	<0.001	20	0.20	0.003	0.15	2.6	0.62	2.3	<0.1	1.01	<1	0.7	1.4
1419668	Rock	0.037	10	6	0.10	300	<0.001	<20	0.20	0.003	0.15	1.6	0.67	2.4	<0.1	0.76	<1	0.9	1.0
1419669	Rock	0.025	14	7	0.25	244	<0.001	<20	0.22	<0.001	0.17	2.0	0.53	1.9	<0.1	0.77	<1	1.1	1.0
1419670	Rock Pulp	0.058	5	32	0.73	98	0.132	<20	1.52	0.084	0.13	10.0	0.04	4.8	<0.1	<0.05	5	<0.5	<0.2
1419671	Rock	0.033	15	6	0.48	984	<0.001	<20	0.24	0.002	0.20	1.3	0.71	2.9	<0.1	0.32	<1	<0.5	<0.2
1419672	Rock	0.029	13	7	0.46	154	<0.001	<20	0.26	0.002	0.23	1.3	0.55	1.9	<0.1	0.69	<1	<0.5	0.2
1419673	Rock	0.035	14	7	0.38	489	<0.001	<20	0.22	0.004	0.18	1.8	0.47	2.0	<0.1	0.60	<1	<0.5	0.2
1419674	Rock	0.030	10	7	0.35	272	<0.001	<20	0.25	0.002	0.19	2.3	0.84	1.7	<0.1	0.66	<1	0.6	0.7
1419675	Rock	0.036	9	7	0.42	50	<0.001	<20	0.24	0.002	0.21	3.5	0.82	2.1	<0.1	1.50	<1	1.0	0.5
1419676	Rock	0.024	14	6	0.43	770	<0.001	<20	0.23	0.003	0.19	1.8	0.57	2.0	<0.1	0.39	<1	0.5	<0.2
1419677	Rock	0.015	19	11	0.53	1454	<0.001	<20	0.20	0.025	0.15	0.7	0.46	3.2	<0.1	0.13	<1	<0.5	<0.2
1419678	Rock	0.010	13	9	0.32	1145	<0.001	<20	0.21	0.012	0.16	0.7	0.95	1.8	0.1	0.25	<1	<0.5	<0.2
1419679	Rock	0.009	13	9	0.31	997	<0.001	<20	0.24	0.019	0.17	0.5	0.44	1.5	<0.1	0.27	<1	<0.5	<0.2
1419680	Rock	0.014	<1	<1	11.87	21	<0.001	<20	0.04	<0.001	0.03	<0.1	0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1456550	Rock	0.017	<1	<1	11.95	33	<0.001	<20	0.03	<0.001	0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1456551	Rock	0.019	26	7	0.10	2222	0.003	<20	0.54	0.013	0.16	0.4	0.25	3.0	<0.1	0.06	2	<0.5	<0.2
1456552	Rock	0.046	17	19	0.09	2228	0.002	<20	0.55	0.007	0.27	0.4	0.69	11.2	0.1	0.06	2	<0.5	<0.2
1456553	Rock	0.116	16	12	0.11	1656	0.003	<20	0.58	0.002	0.37	0.5	0.39	12.9	0.2	<0.05	2	<0.5	<0.2
1456554	Rock	0.097	19	17	0.13	3396	0.005	<20	0.74	0.007	0.33	0.7	0.53	19.7	0.2	0.09	2	<0.5	<0.2
1456555	Rock	0.035	19	19	0.07	3667	0.003	<20	0.50	0.002	0.22	1.1	0.45	9.8	0.2	0.11	2	<0.5	<0.2
1456556	Rock	0.032	18	14	0.06	1592	0.002	<20	0.42	0.004	0.27	0.7	0.35	6.0	0.1	<0.05	1	<0.5	<0.2
1456557	Rock	0.023	14	21	0.06	1886	0.001	<20	0.31	0.002	0.22	0.7	0.21	7.9	0.1	<0.05	1	<0.5	<0.2
1456558	Rock	0.039	12	16	0.05	1956	0.001	<20	0.29	0.001	0.16	1.9	0.34	6.0	0.2	<0.05	<1	<0.5	0.3
1456559	Rock	0.065	11	27	0.14	2218	0.002	<20	0.42	0.001	0.30	0.6	0.09	8.7	0.1	<0.05	1	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 5 of 5 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456560	Rock	2.57	0.018	12.9	3.6	5.2	46	<0.1	34.4	14.8	559	3.16	33.6	21.5	13.2	220	0.3	0.7	<0.1	28	6.64
1456561	Rock	2.55	0.066	4.4	9.6	6.1	36	<0.1	52.1	12.3	461	2.48	25.6	60.7	19.9	116	0.1	1.0	<0.1	27	1.94
1456562	Rock	2.17	0.011	5.7	4.9	4.6	28	<0.1	46.7	12.2	476	2.41	23.4	28.6	21.8	151	<0.1	0.6	<0.1	21	2.00
1456563	Rock	2.62	0.023	8.0	7.6	4.6	27	<0.1	38.7	11.6	384	2.41	19.4	19.1	13.9	166	0.1	0.4	<0.1	22	3.64
1456564	Rock	1.99	0.226	6.4	17.3	7.1	26	0.3	31.3	10.2	358	2.15	13.9	210.7	28.7	150	<0.1	1.2	<0.1	23	1.98
1456565	Rock	1.39	0.225	8.6	38.2	10.9	34	0.3	43.6	12.3	464	2.41	15.3	199.8	11.5	149	0.2	2.9	0.2	32	2.73
1456566	Rock	1.03	0.315	7.5	41.6	14.3	36	0.5	39.2	12.3	601	2.20	13.0	238.0	7.8	143	0.2	1.5	0.2	28	2.48
1456567	Rock	1.31	0.235	6.2	24.6	7.3	34	0.2	39.7	12.0	584	2.37	39.9	120.0	9.8	153	0.2	3.1	0.1	25	2.34
1456568	Rock	1.88	1.573	12.8	53.8	10.1	72	1.1	113.1	21.9	1154	3.67	113.8	1367.1	24.3	166	0.4	7.6	0.1	46	1.52
1456569	Rock	1.47	0.342	9.6	30.4	11.6	70	0.3	127.8	20.8	1011	3.21	173.0	241.4	28.9	140	0.3	2.5	<0.1	38	0.69
1456570	Rock Pulp	0.12	0.772	4.4	33.4	5.3	49	0.3	23.2	9.2	370	2.41	6.3	650.1	0.9	42	0.2	0.8	<0.1	55	0.80
1456571	Rock	2.39	0.125	8.9	24.2	11.2	44	0.2	59.9	18.9	873	3.06	92.5	107.0	35.6	127	0.2	3.1	0.1	40	0.59
1456572	Rock	2.10	0.372	17.4	11.8	8.6	57	0.1	20.5	19.9	1875	4.96	28.2	196.0	39.7	177	0.2	2.1	0.1	71	0.67
1456573	Rock	2.80	0.017	7.0	11.7	5.7	53	<0.1	16.2	24.0	909	4.69	8.1	11.9	20.1	81	0.1	1.8	0.1	116	0.31
1456574	Rock	2.58	0.019	4.9	10.3	5.9	27	<0.1	41.6	13.2	513	2.50	12.6	15.4	27.8	96	<0.1	1.1	0.1	28	1.20
1456575	Rock	1.74	0.222	5.5	18.4	6.5	28	0.3	33.5	10.2	544	2.13	14.4	233.2	15.3	141	0.1	2.6	<0.1	20	3.85
1456576	Rock	1.58	0.428	4.8	40.6	11.4	43	0.5	42.5	11.1	533	2.51	21.1	351.1	13.1	137	0.2	5.0	0.1	23	2.65
1456577	Rock	2.84	0.214	6.3	7.7	12.7	36	0.5	28.3	8.1	813	2.03	12.2	204.3	11.7	164	0.2	0.8	<0.1	12	2.70
1456578	Rock	1.53	0.131	8.7	24.4	19.1	58	0.2	59.2	12.0	413	2.74	67.3	116.9	27.1	110	0.2	2.8	0.1	26	2.13
1456579	Rock	4.60	0.032	4.2	11.8	10.9	26	<0.1	22.0	4.6	228	1.33	22.8	36.2	7.0	77	<0.1	1.2	<0.1	10	0.72
1456580	Rock	0.32	<0.005	0.2	2.1	2.2	16	<0.1	1.7	0.7	214	0.41	0.6	<0.5	0.2	47	<0.1	<0.1	<0.1	<2	18.29
1456581	Rock	1.06	0.020	3.3	8.0	11.0	20	<0.1	14.4	3.7	233	1.05	16.8	15.8	2.6	77	0.1	0.8	<0.1	6	0.76
1456582	Rock	1.19	0.026	10.6	47.9	21.0	55	0.1	42.5	12.7	675	2.51	120.5	22.2	3.8	96	0.3	8.5	0.2	25	0.58



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 5 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000366.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1456560	Rock	0.081	11	24	0.14	2049	0.002	<20	0.43	0.002	0.31	0.7	0.07	9.8	0.2	<0.05	1	<0.5	<0.2	
1456561	Rock	0.018	9	42	0.16	867	0.002	<20	0.44	0.013	0.21	0.4	0.27	8.5	0.1	<0.05	2	<0.5	<0.2	
1456562	Rock	0.027	10	29	0.16	1592	0.002	<20	0.53	0.013	0.30	0.3	0.25	6.9	0.2	<0.05	2	<0.5	<0.2	
1456563	Rock	0.028	10	22	0.17	1706	0.002	<20	0.49	0.003	0.31	0.2	0.15	6.0	0.2	<0.05	2	<0.5	<0.2	
1456564	Rock	0.013	19	17	0.14	1819	0.002	<20	0.51	0.004	0.29	0.2	0.60	6.3	0.1	<0.05	2	<0.5	0.3	
1456565	Rock	0.010	10	26	0.15	1292	0.002	<20	0.40	0.002	0.24	0.4	1.11	7.1	0.2	<0.05	1	<0.5	0.4	
1456566	Rock	0.014	9	21	0.13	938	<0.001	<20	0.39	0.002	0.25	0.3	0.53	6.3	0.1	<0.05	1	<0.5	0.5	
1456567	Rock	0.024	14	23	0.28	2418	0.010	<20	0.58	0.009	0.17	1.1	0.29	6.8	0.1	0.06	2	<0.5	<0.2	
1456568	Rock	0.051	23	65	0.26	2286	0.006	<20	0.52	0.005	0.32	0.5	0.50	10.5	0.2	0.06	2	<0.5	0.7	
1456569	Rock	0.015	12	53	0.11	2163	0.002	<20	0.46	0.002	0.24	0.5	0.39	8.8	0.2	0.05	2	<0.5	<0.2	
1456570	Rock Pulp	0.049	5	31	0.70	91	0.137	<20	1.47	0.080	0.12	9.8	0.05	4.8	<0.1	<0.05	5	<0.5	<0.2	
1456571	Rock	0.032	16	28	0.25	1625	0.010	<20	0.89	0.007	0.41	0.3	0.31	8.8	0.2	<0.05	3	<0.5	<0.2	
1456572	Rock	0.131	18	11	0.53	3088	0.013	<20	1.22	0.006	0.75	0.4	0.39	17.6	0.6	0.07	3	<0.5	<0.2	
1456573	Rock	0.078	14	25	0.78	1031	0.041	<20	1.39	0.017	0.95	0.2	0.45	20.7	0.8	<0.05	4	<0.5	<0.2	
1456574	Rock	0.030	20	28	0.28	1009	0.013	<20	0.79	0.008	0.41	0.4	0.19	6.0	0.2	<0.05	2	<0.5	<0.2	
1456575	Rock	0.020	16	20	0.20	777	0.002	<20	0.41	0.005	0.27	0.3	0.36	6.6	0.1	<0.05	1	<0.5	<0.2	
1456576	Rock	0.037	15	22	0.32	914	0.003	<20	0.46	0.007	0.23	0.4	0.45	7.1	0.1	0.05	1	<0.5	0.4	
1456577	Rock	0.023	12	11	0.13	2699	0.001	<20	0.45	0.005	0.20	0.3	0.20	5.7	<0.1	0.07	1	<0.5	0.4	
1456578	Rock	0.021	15	26	0.17	1064	0.002	<20	0.48	0.004	0.23	0.3	0.19	8.3	0.1	<0.05	1	<0.5	<0.2	
1456579	Rock	0.009	7	21	0.11	1180	0.001	<20	0.47	0.014	0.20	<0.1	0.11	3.0	<0.1	<0.05	1	<0.5	<0.2	
1456580	Rock	0.013	<1	<1	11.22	157	0.002	<20	0.09	<0.001	0.07	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2	
1456581	Rock	0.006	5	14	0.11	1389	<0.001	<20	0.40	0.015	0.18	0.1	0.12	1.9	0.1	<0.05	1	<0.5	<0.2	
1456582	Rock	0.023	10	45	0.12	1714	0.002	<20	0.54	0.013	0.18	0.6	0.16	5.5	0.1	<0.05	2	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Project: QV
Report Date: November 03, 2016

Page: 1 of 2 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000366.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1419624	Rock	1.70	2.896	3.6	13.8	15.6	22	0.2	1.9	2.9	403	1.88	37.1	224.2	8.8	72	0.1	0.3	0.2	9	1.14
REP 1419624	QC			3.3	13.2	15.4	21	0.2	1.8	2.8	411	1.88	35.8	532.3	9.0	68	<0.1	0.3	0.2	9	1.14
1419654	Rock	5.92	0.624	13.0	23.3	21.7	59	1.1	2.1	5.3	504	2.70	8.8	589.1	11.5	82	0.4	1.2	0.2	13	1.07
REP 1419654	QC		0.627																		
1419659	Rock	1.65	0.489	17.1	16.3	11.5	35	1.3	2.8	5.9	643	2.47	11.8	2937.1	9.4	125	0.1	2.2	0.2	12	1.64
REP 1419659	QC			18.5	17.5	11.0	33	1.0	3.1	5.1	662	2.52	11.6	384.4	9.5	123	0.1	2.2	0.3	12	1.68
1456563	Rock	2.62	0.023	8.0	7.6	4.6	27	<0.1	38.7	11.6	384	2.41	19.4	19.1	13.9	166	0.1	0.4	<0.1	22	3.64
REP 1456563	QC			8.0	8.5	4.7	28	<0.1	38.8	11.5	388	2.46	20.2	19.5	13.4	174	0.1	0.4	<0.1	23	3.70
1456580	Rock	0.32	<0.005	0.2	2.1	2.2	16	<0.1	1.7	0.7	214	0.41	0.6	<0.5	0.2	47	<0.1	<0.1	<0.1	<2	18.29
REP 1456580	QC			<0.1	1.8	2.3	15	<0.1	1.9	0.5	220	0.44	<0.5	<0.5	0.2	52	<0.1	<0.1	<0.1	<2	18.80
1456582	Rock	1.19	0.026	10.6	47.9	21.0	55	0.1	42.5	12.7	675	2.51	120.5	22.2	3.8	96	0.3	8.5	0.2	25	0.58
REP 1456582	QC		0.023																		
Core Reject Duplicates																					
1419605	Rock	2.09	0.026	1.9	11.1	24.5	18	<0.1	2.3	2.1	360	1.70	13.4	19.5	13.0	31	<0.1	0.3	0.6	5	0.06
DUP 1419605	QC		0.030	1.7	12.1	23.5	17	<0.1	1.7	2.0	363	1.69	13.7	19.3	12.7	30	<0.1	0.4	0.5	5	0.06
1419639	Rock	1.95	0.029	2.9	10.6	11.4	22	0.1	1.7	3.1	274	1.90	13.7	29.5	7.8	63	<0.1	0.4	0.6	3	0.67
DUP 1419639	QC		0.026	2.7	10.8	11.3	22	0.1	1.6	3.3	279	1.93	13.7	25.6	8.1	64	<0.1	0.5	0.6	3	0.68
1419673	Rock	1.96	0.640	11.7	4.0	5.8	11	0.3	2.5	5.2	591	1.93	3.6	844.2	15.8	89	0.1	0.4	0.1	8	1.14
DUP 1419673	QC		0.818	12.0	4.1	5.7	12	0.3	2.7	5.5	608	2.01	4.0	543.3	16.9	94	<0.1	0.3	0.1	8	1.17
1456573	Rock	2.80	0.017	7.0	11.7	5.7	53	<0.1	16.2	24.0	909	4.69	8.1	11.9	20.1	81	0.1	1.8	0.1	116	0.31
DUP 1456573	QC		0.016	7.1	10.2	5.3	49	<0.1	14.9	22.7	899	4.64	7.7	14.2	19.5	84	0.2	2.0	0.1	117	0.30
Reference Materials																					
STD DS10	Standard			16.1	160.8	154.1	379	2.0	76.6	12.8	883	2.76	45.0	92.7	7.5	65	2.9	8.4	12.4	41	1.04
STD DS10	Standard			14.5	176.5	142.9	340	1.6	71.4	12.0	869	2.68	42.4	223.3	7.3	66	2.7	7.0	12.0	43	1.04
STD DS10	Standard			13.8	161.7	146.6	347	1.7	75.3	13.1	841	2.70	44.2	62.0	7.4	66	2.7	7.3	11.9	40	1.04
STD DS10	Standard			14.4	159.9	147.0	361	2.0	73.2	13.0	872	2.74	46.4	86.3	7.1	69	2.7	7.3	12.8	41	1.06
STD OREAS45EA	Standard			1.5	677.0	14.4	29	0.2	387.2	51.2	397	21.40	9.8	42.0	9.8	3	<0.1	0.4	0.2	298	0.03
STD OREAS45EA	Standard			1.6	708.3	14.3	34	0.3	398.7	50.3	423	21.34	11.0	53.2	10.3	4	<0.1	0.3	0.2	305	0.03



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QV
Report Date: November 03, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000366.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1419624	Rock	0.013	16	4	0.04	1521	<0.001	<20	0.34	0.004	0.20	0.3	0.25	4.3	<0.1	<0.05	<1	<0.5	0.3
REP 1419624	QC	0.013	15	4	0.04	1506	<0.001	<20	0.34	0.003	0.21	0.3	0.23	4.0	<0.1	<0.05	<1	<0.5	<0.2
1419654	Rock	0.054	32	6	0.22	599	0.032	<20	0.44	0.034	0.32	1.8	1.13	4.3	0.1	0.54	3	<0.5	1.4
REP 1419654	QC																		
1419659	Rock	0.057	23	8	0.10	1266	0.007	<20	0.38	0.028	0.26	0.8	0.53	4.0	0.1	0.18	2	<0.5	0.6
REP 1419659	QC	0.048	21	8	0.10	1175	0.006	<20	0.37	0.028	0.26	0.9	0.53	4.1	0.2	0.18	2	<0.5	0.7
1456563	Rock	0.028	10	22	0.17	1706	0.002	<20	0.49	0.003	0.31	0.2	0.15	6.0	0.2	<0.05	2	<0.5	<0.2
REP 1456563	QC	0.027	9	24	0.17	1695	0.002	<20	0.50	0.003	0.32	0.2	0.15	5.9	0.2	<0.05	2	<0.5	<0.2
1456580	Rock	0.013	<1	<1	11.22	157	0.002	<20	0.09	<0.001	0.07	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
REP 1456580	QC	0.014	<1	<1	11.69	183	0.001	<20	0.10	<0.001	0.07	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2
1456582	Rock	0.023	10	45	0.12	1714	0.002	<20	0.54	0.013	0.18	0.6	0.16	5.5	0.1	<0.05	2	<0.5	<0.2
REP 1456582	QC																		
Core Reject Duplicates																			
1419605	Rock	0.003	17	5	0.05	1008	<0.001	<20	0.28	0.004	0.16	0.9	0.19	2.1	<0.1	<0.05	1	<0.5	<0.2
DUP 1419605	QC	0.003	17	4	0.05	1010	<0.001	<20	0.29	0.004	0.16	1.0	0.18	2.1	<0.1	<0.05	1	<0.5	<0.2
1419639	Rock	0.005	12	3	0.03	678	<0.001	<20	0.29	0.006	0.17	0.3	0.22	2.7	<0.1	<0.05	<1	<0.5	0.2
DUP 1419639	QC	0.005	12	4	0.03	652	<0.001	<20	0.32	0.007	0.19	0.2	0.22	2.8	<0.1	<0.05	<1	<0.5	<0.2
1419673	Rock	0.035	14	7	0.38	489	<0.001	<20	0.22	0.004	0.18	1.8	0.47	2.0	<0.1	0.60	<1	<0.5	0.2
DUP 1419673	QC	0.036	16	7	0.39	416	<0.001	<20	0.24	0.004	0.19	2.1	0.47	1.9	<0.1	0.62	<1	<0.5	0.3
1456573	Rock	0.078	14	25	0.78	1031	0.041	<20	1.39	0.017	0.95	0.2	0.45	20.7	0.8	<0.05	4	<0.5	<0.2
DUP 1456573	QC	0.076	14	24	0.76	934	0.043	<20	1.39	0.018	0.95	0.3	0.43	21.9	0.8	<0.05	4	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.072	18	54	0.77	431	0.077	<20	1.04	0.071	0.33	3.3	0.28	2.8	5.0	0.29	4	1.5	5.6
STD DS10	Standard	0.069	17	58	0.75	366	0.080	<20	1.01	0.069	0.33	2.7	0.24	3.0	4.9	0.28	4	2.1	4.6
STD DS10	Standard	0.070	17	54	0.76	391	0.081	<20	1.01	0.069	0.32	2.6	0.34	3.0	5.0	0.28	4	1.9	4.9
STD DS10	Standard	0.072	18	51	0.78	421	0.083	<20	1.05	0.073	0.33	2.7	0.27	3.1	5.0	0.28	4	2.3	4.7
STD OREAS45EA	Standard	0.022	7	843	0.08	132	0.091	<20	3.22	0.021	0.05	<0.1	0.02	72.5	<0.1	<0.05	11	0.9	<0.2
STD OREAS45EA	Standard	0.028	7	890	0.09	146	0.105	<20	3.28	0.025	0.06	<0.1	<0.01	80.2	<0.1	<0.05	13	1.1	<0.2



QUALITY CONTROL REPORT

WHI16000366.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD OREAS45EA	Standard			1.6	686.1	13.8	30	0.2	403.1	54.5	403	21.44	10.4	48.7	9.9	4	<0.1	0.2	0.3	304	0.03	
STD OREAS45EA	Standard			1.4	669.8	14.8	30	0.3	394.1	51.8	397	20.91	11.3	48.1	9.9	4	<0.1	0.2	0.3	299	0.03	
STD OXD108	Standard		0.410																			
STD OXD108	Standard		0.403																			
STD OXD108	Standard		0.404																			
STD OXI121	Standard		1.831																			
STD OXI121	Standard		1.823																			
STD OXI121	Standard		1.824																			
STD OXN117	Standard		7.734																			
STD OXN117	Standard		7.626																			
STD OXN117	Standard		7.706																			
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
STD OXD108 Expected			0.414																			
STD OXN117 Expected			7.679																			
STD OXI121 Expected			1.834																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
Prep Wash																						
ROCK-WHI	Prep Blank		<0.005	0.8	5.6	1.7	31	<0.1	0.7	3.2	409	1.67	0.8	1.2	2.4	31	<0.1	<0.1	<0.1	22	0.57	
ROCK-WHI	Prep Blank		<0.005	0.7	3.7	1.6	29	<0.1	0.6	3.3	408	1.66	0.8	0.9	2.6	28	<0.1	<0.1	<0.1	22	0.59	



QUALITY CONTROL REPORT

WHI16000366.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OREAS45EA	Standard	0.024	7	817	0.09	139	0.109	<20	3.32	0.021	0.05	<0.1	0.02	81.9	<0.1	<0.05	13	0.9	<0.2	
STD OREAS45EA	Standard	0.032	7	788	0.09	151	0.097	<20	3.27	0.022	0.05	<0.1	0.01	80.0	<0.1	<0.05	12	0.6	<0.2	
STD OXD108	Standard																			
STD OXD108	Standard																			
STD OXD108	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.047	6	2	0.38	79	0.082	<20	0.85	0.080	0.08	0.1	<0.01	2.3	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.039	5	2	0.37	66	0.086	<20	0.87	0.079	0.08	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 02, 2016
Report Date: November 20, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000420.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV-10-30-2016 RAB
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	133	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	138	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456583	Rock	1.86	0.006	0.7	34.0	8.8	69	<0.1	22.7	12.3	343	2.10	2.1	4.1	17.2	29	<0.1	0.1	0.3	15	1.80
1456584	Rock	2.33	<0.005	1.2	18.6	21.3	49	<0.1	30.9	14.1	657	2.77	4.7	1.8	13.6	50	0.1	0.3	0.3	33	3.97
1456585	Rock	1.95	<0.005	0.8	38.5	13.3	48	<0.1	31.6	14.8	904	2.98	4.1	0.8	13.1	132	<0.1	0.1	0.3	43	8.16
1456586	Rock	2.68	0.008	1.3	37.1	6.6	72	<0.1	80.6	26.1	880	4.86	15.2	<0.5	10.1	149	0.1	0.3	0.2	111	6.56
1456587	Rock	1.77	<0.005	0.9	34.8	7.1	60	<0.1	37.0	13.6	737	2.92	7.6	<0.5	10.5	161	0.1	0.3	0.1	54	4.76
1456588	Rock	2.82	<0.005	2.3	55.4	7.0	57	<0.1	87.7	27.7	801	4.55	1.7	1.2	4.7	103	<0.1	0.1	<0.1	121	3.22
1456589	Rock	2.23	<0.005	0.7	116.9	4.5	77	<0.1	138.2	45.4	734	5.86	0.9	<0.5	2.8	75	<0.1	0.2	<0.1	151	1.94
1456590	Rock	2.56	<0.005	0.7	116.7	4.5	75	<0.1	135.6	44.2	715	5.74	0.6	<0.5	2.7	73	<0.1	0.2	<0.1	149	1.78
1456591	Rock	1.81	<0.005	0.6	102.7	16.4	64	<0.1	91.5	34.3	660	4.84	4.1	1.1	4.1	106	<0.1	0.2	0.2	135	2.08
1456592	Rock	3.08	<0.005	0.9	57.7	17.0	63	<0.1	64.2	25.1	718	4.00	2.4	1.0	6.6	190	<0.1	0.1	0.1	102	5.38
1456593	Rock	1.44	<0.005	0.5	48.4	5.6	63	<0.1	64.9	23.1	561	3.91	8.5	<0.5	8.1	70	<0.1	0.1	<0.1	85	3.41
1456594	Rock	1.52	<0.005	0.7	48.2	5.5	57	<0.1	44.9	17.0	639	3.05	4.6	0.5	7.7	127	<0.1	0.2	<0.1	65	3.32
1456595	Rock	1.90	<0.005	0.6	22.1	5.1	43	<0.1	32.5	12.0	467	2.34	5.1	0.8	7.1	76	<0.1	0.1	<0.1	51	2.34
1456596	Rock	1.48	<0.005	0.7	22.1	7.9	43	<0.1	24.6	10.4	511	2.30	6.0	<0.5	13.5	89	<0.1	0.2	<0.1	43	2.76
1456597	Rock	1.72	0.052	0.7	27.7	8.6	43	<0.1	48.1	13.8	507	2.32	1.9	<0.5	6.9	132	<0.1	0.1	<0.1	55	2.71
1456598	Rock	2.12	<0.005	0.9	33.6	8.4	56	<0.1	69.9	20.0	651	3.36	5.3	<0.5	11.6	99	<0.1	0.2	0.1	67	2.52
1456599	Rock	2.29	<0.005	0.8	20.1	8.9	47	<0.1	20.7	11.0	643	2.90	19.4	<0.5	19.3	33	<0.1	0.5	0.2	27	0.74
1456600	Rock Pulp	0.12	2.185	64.7	2183.6	1272.9	3759	25.0	183.5	20.3	637	5.13	1195.0	1334.5	2.7	89	21.1	17.0	11.6	54	1.46
1456601	Rock	2.16	0.038	1.3	16.4	8.8	47	0.1	17.3	10.5	639	2.59	11.0	30.6	18.4	32	<0.1	0.6	0.2	21	1.34
1456602	Rock	2.25	0.058	1.0	24.5	9.6	38	0.1	16.4	9.6	515	2.38	4.4	187.4	17.9	28	<0.1	0.2	0.2	16	1.54
1456603	Rock	2.84	0.030	2.0	35.6	18.7	41	0.1	36.5	15.6	628	3.07	21.9	22.1	11.1	66	<0.1	0.5	0.3	46	3.08
1456604	Rock	2.13	<0.005	1.5	23.6	9.7	44	<0.1	45.9	18.0	848	3.60	28.2	11.9	14.2	181	0.1	0.5	0.1	64	5.10
1456605	Rock	2.17	<0.005	1.2	20.0	4.9	49	<0.1	39.2	16.0	600	3.40	14.0	<0.5	11.0	80	<0.1	0.2	<0.1	56	2.26
1456606	Rock	2.36	0.064	1.3	35.9	5.7	74	<0.1	46.6	22.9	784	4.49	8.3	284.3	7.3	71	<0.1	0.3	0.1	60	4.71
1456607	Rock	2.31	0.008	2.1	43.9	18.6	74	<0.1	41.0	16.9	664	3.67	22.9	16.1	7.7	88	<0.1	1.6	0.3	42	3.15
1456608	Rock	2.08	0.101	2.9	35.7	14.4	70	0.1	32.8	14.1	396	3.21	42.0	71.9	9.1	58	<0.1	2.6	0.2	21	1.48
1456609	Rock	1.97	0.809	28.1	15.2	24.5	43	1.2	31.1	12.5	695	2.80	87.7	809.2	2.8	75	0.2	2.7	0.6	21	3.76
1456610	Rock Pulp	0.12	0.805	4.2	32.2	5.4	49	0.4	23.1	8.9	397	2.53	6.4	1685.8	1.0	44	0.2	0.9	0.1	59	0.85
1456611	Rock	1.83	0.095	4.1	6.4	9.7	13	0.1	2.9	3.2	182	1.44	40.7	103.2	4.6	84	<0.1	1.4	<0.1	6	0.33
1456612	Rock	2.38	0.323	2.5	11.0	21.6	30	0.1	2.3	2.6	329	2.00	77.1	339.9	11.7	78	<0.1	2.0	<0.1	11	0.56



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1456583	Rock	0.063	53	17	0.50	165	0.069	<20	0.98	0.016	0.67	1.2	0.04	2.8	0.2	<0.05	3	<0.5	<0.2
1456584	Rock	0.078	43	29	0.86	220	0.058	<20	1.30	0.013	0.84	1.0	0.08	5.7	0.2	<0.05	4	<0.5	<0.2
1456585	Rock	0.086	44	54	1.53	479	0.130	<20	1.74	0.019	1.16	0.5	0.08	6.6	0.3	<0.05	7	<0.5	<0.2
1456586	Rock	0.145	45	169	2.21	569	0.135	<20	2.46	0.020	1.01	0.2	0.05	12.8	0.4	<0.05	11	0.5	<0.2
1456587	Rock	0.084	36	60	0.71	385	0.029	<20	0.99	0.020	0.33	0.3	0.03	7.3	0.1	<0.05	6	<0.5	<0.2
1456588	Rock	0.213	18	168	2.49	452	0.305	<20	2.84	0.042	2.10	0.1	0.01	8.7	0.4	<0.05	10	<0.5	<0.2
1456589	Rock	0.329	24	335	3.55	413	0.365	<20	3.24	0.034	2.56	<0.1	<0.01	6.5	0.6	<0.05	14	<0.5	<0.2
1456590	Rock	0.324	23	326	3.45	407	0.346	<20	3.16	0.035	2.52	<0.1	<0.01	6.4	0.6	<0.05	14	<0.5	<0.2
1456591	Rock	0.256	26	217	2.90	944	0.368	<20	2.65	0.029	2.20	0.2	<0.01	6.9	0.6	<0.05	12	<0.5	<0.2
1456592	Rock	0.191	26	147	2.58	795	0.332	<20	2.48	0.035	2.11	0.2	<0.01	8.8	0.6	<0.05	11	<0.5	<0.2
1456593	Rock	0.171	26	122	2.43	488	0.295	<20	2.57	0.041	1.84	0.2	<0.01	6.6	0.4	<0.05	11	<0.5	<0.2
1456594	Rock	0.111	21	86	1.72	394	0.247	<20	1.89	0.030	1.46	0.3	<0.01	5.7	0.4	<0.05	8	<0.5	<0.2
1456595	Rock	0.072	16	76	1.18	278	0.179	<20	1.34	0.037	1.02	0.8	<0.01	4.8	0.3	<0.05	6	<0.5	<0.2
1456596	Rock	0.043	27	65	1.11	134	0.161	<20	1.36	0.033	1.09	0.5	<0.01	5.4	0.4	<0.05	6	<0.5	<0.2
1456597	Rock	0.073	15	110	1.34	227	0.201	<20	1.38	0.056	1.12	0.8	<0.01	4.6	0.3	<0.05	5	<0.5	<0.2
1456598	Rock	0.090	31	154	1.71	482	0.211	<20	1.87	0.024	1.54	0.3	<0.01	7.4	0.5	<0.05	7	<0.5	<0.2
1456599	Rock	0.054	51	30	0.63	180	0.114	<20	1.18	0.026	0.92	0.3	<0.01	4.4	0.3	<0.05	5	<0.5	<0.2
1456600	Rock Pulp	0.066	12	44	0.86	285	0.096	<20	1.51	0.081	0.19	8.6	0.75	4.5	1.4	1.43	6	3.5	0.5
1456601	Rock	0.043	45	20	0.48	332	0.084	<20	0.96	0.025	0.74	0.4	0.05	3.9	0.2	<0.05	4	<0.5	<0.2
1456602	Rock	0.053	32	16	0.22	355	0.039	<20	0.69	0.024	0.52	0.3	0.05	3.9	0.2	<0.05	3	<0.5	<0.2
1456603	Rock	0.136	31	56	0.54	292	0.059	<20	0.87	0.015	0.66	0.7	0.06	7.0	0.3	<0.05	4	<0.5	<0.2
1456604	Rock	0.102	42	92	1.00	533	0.120	<20	1.27	0.026	1.06	0.2	0.04	10.2	0.3	<0.05	6	<0.5	<0.2
1456605	Rock	0.091	22	76	0.92	694	0.116	<20	1.31	0.021	1.09	0.4	0.02	8.5	0.3	<0.05	6	<0.5	<0.2
1456606	Rock	0.210	25	67	0.95	829	0.096	<20	1.50	0.016	1.18	0.2	0.15	11.0	0.3	<0.05	5	<0.5	<0.2
1456607	Rock	0.077	22	26	0.19	1590	0.009	<20	0.59	0.016	0.37	0.4	0.29	8.6	0.3	<0.05	2	<0.5	<0.2
1456608	Rock	0.021	27	14	0.09	521	0.002	<20	0.44	0.008	0.30	0.2	0.37	4.6	0.3	<0.05	1	<0.5	<0.2
1456609	Rock	0.014	5	18	0.08	1702	<0.001	<20	0.29	0.002	0.15	0.5	0.77	9.6	0.4	<0.05	<1	<0.5	2.0
1456610	Rock Pulp	0.059	5	31	0.74	101	0.134	<20	1.57	0.085	0.13	10.2	0.05	5.1	<0.1	<0.05	5	<0.5	<0.2
1456611	Rock	0.006	7	6	0.03	4593	<0.001	<20	0.18	0.001	0.09	2.3	0.30	1.6	0.1	0.14	<1	<0.5	<0.2
1456612	Rock	0.016	19	7	0.05	3455	<0.001	<20	0.33	0.009	0.16	0.9	0.23	4.2	0.1	0.08	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456613	Rock	2.22	0.419	3.6	9.7	20.9	27	0.3	1.5	1.8	358	1.62	43.8	606.1	14.3	62	<0.1	1.9	0.2	8	0.47
1456614	Rock	2.32	0.227	5.4	5.0	14.7	32	0.2	1.2	1.6	440	1.48	71.4	285.2	10.6	52	<0.1	1.2	0.1	6	1.16
1456615	Rock	2.01	0.038	2.8	4.0	11.0	37	<0.1	1.1	2.1	458	1.70	94.0	28.9	8.5	77	<0.1	1.2	0.2	7	1.37
1456616	Rock	2.27	0.043	1.7	5.4	31.7	59	<0.1	1.3	4.0	788	2.41	87.0	42.2	12.3	109	0.1	2.3	0.2	13	2.62
1456617	Rock	2.52	0.018	1.0	8.3	27.0	41	<0.1	1.0	2.1	530	2.00	42.5	15.4	12.9	88	<0.1	3.6	<0.1	19	1.95
1456618	Rock	2.50	0.010	1.1	26.9	14.4	53	<0.1	1.3	3.0	507	2.22	16.0	11.9	10.7	63	<0.1	6.7	<0.1	9	1.11
1456619	Rock	2.30	0.011	1.3	19.5	116.6	43	0.4	1.4	3.8	619	2.07	19.9	10.1	9.9	63	<0.1	4.7	1.4	15	1.30
1456620	Rock	0.53	<0.005	0.1	1.1	2.4	16	<0.1	1.6	1.0	250	0.44	0.9	2.5	0.2	52	<0.1	<0.1	<0.1	<2	21.23
1456621	Rock	2.34	0.006	5.5	6.0	23.5	37	<0.1	1.0	2.7	478	1.95	19.8	4.9	7.3	106	<0.1	1.7	0.2	6	1.68
1456622	Rock	2.48	0.006	2.0	4.4	15.6	38	<0.1	1.7	3.0	506	1.90	18.9	4.7	9.2	67	<0.1	1.5	0.1	4	0.96
1456623	Rock	2.28	<0.005	3.2	5.7	8.4	40	<0.1	1.1	3.3	577	2.05	24.0	4.5	9.3	66	<0.1	1.6	0.2	5	1.21
1456624	Rock	1.87	<0.005	1.4	5.8	6.5	36	<0.1	1.1	3.4	598	1.85	24.6	10.1	13.9	82	<0.1	2.0	0.2	7	1.39
1456625	Rock	2.64	0.013	1.4	5.0	4.3	50	<0.1	1.9	4.1	646	2.10	7.9	9.5	16.2	51	<0.1	0.6	0.2	10	0.88
1456626	Rock	2.33	<0.005	1.6	3.1	4.9	41	<0.1	1.8	3.7	605	1.83	7.5	2.9	20.0	42	<0.1	0.5	0.2	7	0.80
1456627	Rock	2.36	0.005	3.0	4.6	8.1	42	<0.1	1.7	3.5	572	1.85	10.3	2.9	16.5	58	<0.1	1.4	0.1	8	1.23
1456628	Rock	2.13	<0.005	1.4	2.9	7.5	46	<0.1	1.1	3.0	575	2.02	20.5	<0.5	14.1	73	<0.1	1.6	<0.1	2	1.12
1456629	Rock	2.50	0.037	1.8	4.3	7.8	48	<0.1	1.7	2.7	495	1.77	11.2	23.8	18.3	49	<0.1	1.4	<0.1	7	0.92
1456630	Rock	1.85	<0.005	1.6	2.7	7.8	50	<0.1	0.8	3.0	622	2.09	20.0	1.0	14.6	82	<0.1	1.9	<0.1	2	1.26
1456631	Rock	2.94	0.011	3.1	6.0	8.0	30	<0.1	1.3	2.7	452	1.46	42.2	2.4	13.5	46	<0.1	1.7	0.1	2	0.61
1456632	Rock	2.49	<0.005	2.4	9.7	10.2	50	<0.1	0.8	3.4	540	2.12	22.6	1.5	11.7	53	<0.1	2.1	0.2	3	1.03
1456633	Rock	1.87	<0.005	1.9	7.3	10.5	49	<0.1	1.3	3.8	575	1.90	66.3	1.4	12.8	55	<0.1	2.7	0.1	3	0.65
1456634	Rock	2.45	<0.005	2.9	9.9	4.6	48	<0.1	1.1	3.0	581	1.79	26.1	<0.5	17.1	83	<0.1	1.7	0.2	3	1.20
1456635	Rock	2.53	0.005	2.9	15.6	6.4	40	<0.1	2.2	3.1	555	1.45	24.3	6.4	17.2	99	<0.1	1.4	0.5	3	1.03
1456636	Rock	2.20	0.027	2.9	17.5	5.8	37	<0.1	1.1	2.3	653	1.50	20.7	15.9	15.9	138	<0.1	0.9	0.3	3	1.53
1456637	Rock	2.24	0.163	2.7	18.1	8.1	33	0.1	0.9	2.1	526	1.48	21.2	90.9	14.9	102	<0.1	1.5	0.1	6	1.27
1456638	Rock	2.37	0.059	2.3	27.6	7.9	41	<0.1	2.6	2.6	386	1.62	9.2	50.8	14.3	74	<0.1	2.0	0.2	13	0.79
1456639	Rock	2.47	0.122	2.2	10.1	6.0	24	<0.1	2.0	1.6	362	1.16	10.0	73.9	16.9	119	<0.1	1.9	0.1	7	1.60
1456640	Rock Pulp	0.12	2.336	62.9	2162.3	1273.5	3713	25.4	181.6	19.9	629	5.06	1195.8	1258.0	2.6	80	20.9	16.2	10.4	53	1.45
1456641	Rock	2.13	0.010	2.1	13.5	4.6	18	<0.1	1.9	1.4	264	1.17	16.0	8.6	16.5	89	<0.1	1.6	0.1	5	0.64
1456642	Rock	2.31	<0.005	2.2	16.2	3.3	29	<0.1	3.1	2.7	422	1.58	13.1	5.2	15.4	66	<0.1	1.5	0.3	13	0.59



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method Analyte Unit	AQ200 P	AQ200 La	AQ200 Cr	AQ200 Mg	AQ200 Ba	AQ200 Ti	AQ200 B	AQ200 Al	AQ200 Na	AQ200 K	AQ200 W	AQ200 Hg	AQ200 Sc	AQ200 Ti	AQ200 S	AQ200 Ga	AQ200 Se	AQ200 Te	MDL	
																			%	ppm
1456613	Rock	0.014	21	6	0.04	2113	<0.001	<20	0.27	0.024	0.11	0.7	0.19	3.8	<0.1	0.05	<1	<0.5	0.3	0.2
1456614	Rock	0.009	18	5	0.05	1111	<0.001	<20	0.30	0.009	0.16	0.6	0.13	4.1	0.1	<0.05	<1	<0.5	0.3	0.2
1456615	Rock	0.016	12	5	0.05	1187	<0.001	<20	0.34	0.002	0.19	0.6	0.10	4.5	<0.1	<0.05	<1	<0.5	<0.2	0.2
1456616	Rock	0.038	15	4	0.07	2318	<0.001	<20	0.37	0.004	0.19	0.5	0.18	5.3	0.1	0.06	1	<0.5	<0.2	0.2
1456617	Rock	0.024	18	5	0.07	2044	<0.001	<20	0.25	0.021	0.12	0.6	0.30	4.2	0.2	0.05	<1	<0.5	<0.2	0.2
1456618	Rock	0.024	15	6	0.05	1804	0.001	<20	0.26	0.032	0.14	0.4	0.26	4.3	0.1	<0.05	<1	0.5	<0.2	0.2
1456619	Rock	0.032	13	6	0.05	1226	<0.001	<20	0.24	0.029	0.10	0.8	0.35	4.6	0.3	<0.05	<1	<0.5	<0.2	0.2
1456620	Rock	0.015	<1	<1	10.23	47	<0.001	<20	0.03	0.001	0.02	<0.1	0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2	0.2
1456621	Rock	0.019	10	5	0.29	1668	<0.001	<20	0.28	0.013	0.16	0.4	0.22	3.1	<0.1	0.08	<1	<0.5	<0.2	0.2
1456622	Rock	0.018	13	7	0.12	735	0.001	<20	0.30	0.026	0.18	0.6	0.13	2.9	<0.1	0.07	<1	<0.5	<0.2	0.2
1456623	Rock	0.034	12	6	0.17	429	0.002	<20	0.34	0.022	0.20	0.5	0.13	3.2	<0.1	0.08	1	<0.5	<0.2	0.2
1456624	Rock	0.033	24	7	0.27	533	0.014	<20	0.40	0.033	0.27	1.1	0.16	3.7	0.1	0.12	2	<0.5	<0.2	0.2
1456625	Rock	0.044	36	8	0.41	629	0.072	<20	0.76	0.040	0.59	1.3	0.05	3.3	0.2	0.13	4	<0.5	<0.2	0.2
1456626	Rock	0.033	40	8	0.36	511	0.065	<20	0.72	0.039	0.55	1.2	0.03	2.2	0.2	0.12	4	<0.5	<0.2	0.2
1456627	Rock	0.032	35	8	0.28	502	0.033	<20	0.50	0.033	0.38	1.3	0.08	2.8	0.2	0.08	3	<0.5	<0.2	0.2
1456628	Rock	0.039	22	7	0.15	789	0.006	<20	0.40	0.028	0.29	0.4	0.10	4.0	0.1	<0.05	2	<0.5	<0.2	0.2
1456629	Rock	0.028	40	8	0.31	677	0.053	<20	0.62	0.036	0.48	1.3	0.06	2.5	0.2	<0.05	3	<0.5	<0.2	0.2
1456630	Rock	0.043	24	6	0.16	886	0.006	<20	0.40	0.027	0.29	0.4	0.13	4.4	0.1	<0.05	2	<0.5	<0.2	0.2
1456631	Rock	0.023	17	6	0.11	246	0.002	<20	0.31	0.025	0.23	0.5	0.14	1.8	0.1	<0.05	<1	<0.5	<0.2	0.2
1456632	Rock	0.043	21	6	0.14	589	0.005	<20	0.42	0.023	0.29	0.6	0.18	3.6	<0.1	0.09	2	<0.5	<0.2	0.2
1456633	Rock	0.039	14	6	0.10	498	0.002	<20	0.34	0.019	0.23	0.3	0.19	2.9	<0.1	<0.05	<1	<0.5	<0.2	0.2
1456634	Rock	0.039	45	7	0.28	1322	0.057	<20	0.64	0.030	0.51	0.6	0.11	2.6	0.2	0.09	3	<0.5	<0.2	0.2
1456635	Rock	0.026	30	8	0.35	1207	0.011	<20	0.47	0.021	0.34	0.6	0.18	1.9	0.1	0.07	2	<0.5	<0.2	0.2
1456636	Rock	0.022	25	7	0.52	1423	0.015	<20	0.57	0.020	0.42	0.6	0.17	1.9	0.1	0.09	2	<0.5	<0.2	0.2
1456637	Rock	0.025	29	7	0.38	556	0.004	<20	0.31	0.031	0.21	0.9	0.13	3.6	<0.1	0.10	1	<0.5	<0.2	0.2
1456638	Rock	0.032	35	11	0.47	718	0.036	<20	0.56	0.045	0.38	1.4	0.40	4.9	0.1	0.13	3	<0.5	<0.2	0.2
1456639	Rock	0.009	41	9	0.29	1762	0.008	<20	0.24	0.040	0.15	1.9	0.13	5.3	<0.1	0.13	2	<0.5	<0.2	0.2
1456640	Rock Pulp	0.065	12	44	0.83	243	0.087	<20	1.47	0.079	0.18	8.5	0.74	4.5	1.3	1.40	6	3.4	0.5	0.2
1456641	Rock	0.006	40	9	0.17	2351	0.006	<20	0.28	0.043	0.18	1.8	0.11	3.8	<0.1	0.17	2	<0.5	<0.2	0.2
1456642	Rock	0.022	41	16	0.40	901	0.046	<20	0.64	0.039	0.47	1.5	0.16	5.3	0.2	0.09	4	<0.5	<0.2	0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 4 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method Analyte	Unit	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
			Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
MDL		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
1456643	Rock	1.85	0.029	0.9	9.1	15.1	29	<0.1	2.7	4.0	294	1.53	27.1	29.7	14.5	19	<0.1	0.1	0.2	12	0.54
1456644	Rock	2.26	<0.005	0.8	8.9	9.4	39	<0.1	2.8	5.5	595	1.86	2.1	3.4	17.7	57	0.1	<0.1	<0.1	14	1.80
1456645	Rock	3.98	<0.005	1.1	7.8	7.5	35	<0.1	2.9	5.2	343	1.85	1.1	2.0	20.4	29	<0.1	<0.1	<0.1	16	0.82
1456646	Rock	3.52	<0.005	1.8	6.8	16.6	26	<0.1	2.5	3.7	293	1.44	3.3	3.9	12.6	17	<0.1	<0.1	0.3	12	0.61
1456647	Rock	1.36	0.026	0.9	1.8	24.4	16	0.1	1.1	1.8	298	1.25	3.8	9.3	7.5	18	0.1	0.1	0.5	20	0.61
1456648	Rock	1.58	0.017	0.8	9.1	20.5	50	0.1	2.9	6.6	319	2.03	21.0	18.9	16.6	17	<0.1	<0.1	0.2	13	0.41
1456649	Rock	2.10	0.022	1.5	9.1	21.4	53	0.1	3.0	8.2	615	2.47	41.0	22.3	16.9	19	0.2	0.1	0.2	18	1.08
1456650	Rock	0.32	<0.005	0.1	3.8	1.6	15	<0.1	1.1	1.0	228	0.44	<0.5	0.7	0.2	49	<0.1	<0.1	<0.1	<2	21.03
1456651	Rock	2.20	0.012	1.5	14.4	16.4	41	0.1	2.6	6.7	511	2.17	20.2	12.2	18.5	16	0.1	<0.1	0.2	16	0.79
1456652	Rock	2.13	0.024	1.4	3.8	12.8	51	0.1	3.1	6.9	449	2.16	39.6	21.8	19.2	16	0.1	0.1	<0.1	11	0.77
1456653	Rock	2.20	0.039	1.4	6.4	17.0	38	0.1	2.6	5.8	466	2.01	63.7	39.7	18.0	19	0.1	0.2	0.1	12	1.47
1456654	Rock	1.81	0.033	1.4	8.5	21.8	42	0.1	3.2	6.6	460	2.12	52.3	30.1	17.8	17	0.2	0.2	0.3	13	0.87
1456655	Rock	2.56	<0.005	1.1	6.3	9.7	45	<0.1	3.3	6.4	382	1.99	7.7	1.5	17.3	15	<0.1	<0.1	0.1	13	0.46
1456656	Rock	2.36	<0.005	1.2	15.6	15.0	47	<0.1	3.1	6.5	449	2.03	1.5	1.9	19.2	18	<0.1	<0.1	0.3	26	0.51
1456657	Rock	1.99	<0.005	1.7	5.1	17.0	31	<0.1	2.2	4.5	433	1.72	7.2	1.8	18.5	19	0.1	<0.1	0.3	14	0.55
1456658	Rock	1.92	0.017	1.3	11.8	42.6	48	0.2	3.0	6.8	714	2.29	15.4	2.0	16.7	31	0.5	0.1	0.7	18	2.65
1456659	Rock	2.62	0.006	1.4	10.8	40.8	48	0.3	3.2	6.9	677	2.21	15.2	2.5	16.3	29	0.4	0.1	0.7	17	2.44
1456660	Rock	2.36	<0.005	1.4	5.0	18.2	49	<0.1	6.9	9.8	682	2.48	1.9	<0.5	10.9	27	0.2	<0.1	0.2	34	1.82
1456661	Rock	2.19	<0.005	1.7	5.4	17.5	33	<0.1	3.4	6.2	557	2.07	1.2	0.6	15.6	49	0.1	<0.1	0.2	15	1.95
1456662	Rock	2.03	<0.005	1.0	5.2	18.5	34	<0.1	2.6	5.4	535	1.90	1.3	1.6	17.7	49	<0.1	<0.1	<0.1	11	2.54
1456663	Rock	1.80	0.023	0.8	6.6	15.9	37	<0.1	3.1	5.9	612	1.87	8.5	19.8	16.7	45	0.1	<0.1	0.1	10	1.99
1456664	Rock	1.99	0.020	1.1	7.1	17.9	32	0.1	3.3	5.5	537	1.92	7.9	18.6	18.9	42	0.2	<0.1	0.2	15	1.95
1456665	Rock	2.17	0.033	0.8	6.6	8.6	27	0.1	3.4	4.8	484	1.68	9.0	31.2	17.9	39	<0.1	<0.1	<0.1	13	1.34
1456666	Rock	1.98	0.064	0.5	14.4	11.7	86	0.1	40.3	13.2	982	3.19	18.5	59.0	10.2	48	0.2	<0.1	0.1	38	1.95
1456667	Rock	2.09	0.069	0.7	6.7	11.5	44	0.1	7.6	6.8	712	2.43	17.3	65.2	17.1	49	0.1	0.1	<0.1	18	2.06
1456668	Rock	2.25	0.050	0.6	8.6	14.5	41	<0.1	3.6	5.9	720	2.08	15.9	44.2	18.3	63	0.2	<0.1	<0.1	14	2.23
1456669	Rock	2.30	0.045	0.9	6.5	46.4	36	0.2	2.6	5.4	688	2.01	14.0	45.0	16.4	59	<0.1	0.1	0.2	16	2.40
1456670	Rock Pulp	0.15	0.813	4.2	34.0	6.1	50	0.2	24.6	9.4	403	2.56	6.2	530.9	1.0	43	0.2	0.9	0.1	58	0.84
1456671	Rock	2.27	0.079	1.0	7.7	25.7	25	0.2	2.8	6.7	421	1.47	17.1	73.4	17.5	21	0.1	0.1	<0.1	16	0.53
1456672	Rock	2.19	0.073	2.6	7.8	17.7	23	0.2	2.8	5.7	87	1.51	22.8	70.0	14.4	15	<0.1	0.1	0.2	7	0.13



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456643	Rock	0.031	27	4	0.08	280	0.002	<20	0.44	0.010	0.25	0.7	0.02	1.8	<0.1	<0.05	1	<0.5	<0.2
1456644	Rock	0.041	46	4	0.11	197	0.002	<20	0.61	0.012	0.31	0.5	0.01	1.8	<0.1	<0.05	1	<0.5	<0.2
1456645	Rock	0.048	49	5	0.10	115	0.006	<20	0.54	0.011	0.33	0.9	0.01	2.0	<0.1	<0.05	2	<0.5	<0.2
1456646	Rock	0.029	23	4	0.06	280	0.003	<20	0.41	0.013	0.27	1.0	0.01	1.2	<0.1	<0.05	1	<0.5	<0.2
1456647	Rock	0.011	10	3	0.02	92	0.007	<20	0.21	0.027	0.12	0.9	0.02	1.1	<0.1	<0.05	<1	<0.5	<0.2
1456648	Rock	0.056	36	4	0.08	147	0.002	<20	0.55	0.014	0.32	0.1	0.02	2.5	<0.1	<0.05	2	<0.5	<0.2
1456649	Rock	0.049	39	4	0.10	131	0.003	<20	0.51	0.014	0.30	0.3	0.05	4.3	0.1	<0.05	1	<0.5	<0.2
1456650	Rock	0.017	<1	<1	10.34	28	<0.001	<20	0.03	0.001	0.02	<0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1456651	Rock	0.048	39	4	0.13	128	0.008	<20	0.58	0.009	0.39	0.5	0.02	2.9	0.1	<0.05	2	<0.5	<0.2
1456652	Rock	0.049	39	4	0.13	114	0.006	<20	0.63	0.010	0.41	0.3	0.04	2.4	0.2	<0.05	2	<0.5	<0.2
1456653	Rock	0.047	43	5	0.11	196	0.004	<20	0.53	0.009	0.38	0.4	0.04	2.2	0.1	<0.05	2	<0.5	0.3
1456654	Rock	0.046	42	5	0.14	110	0.006	<20	0.61	0.007	0.40	0.3	0.02	2.7	0.2	<0.05	2	<0.5	<0.2
1456655	Rock	0.047	28	5	0.16	115	0.010	<20	0.72	0.006	0.43	0.3	0.01	2.3	0.2	<0.05	2	<0.5	<0.2
1456656	Rock	0.050	34	5	0.17	118	0.013	<20	0.69	0.009	0.41	0.4	<0.01	3.3	0.2	<0.05	2	<0.5	<0.2
1456657	Rock	0.047	54	4	0.07	331	0.004	<20	0.43	0.012	0.31	0.6	<0.01	2.6	0.1	<0.05	1	<0.5	<0.2
1456658	Rock	0.045	44	5	0.11	88	0.002	<20	0.44	0.018	0.29	0.6	<0.01	3.4	<0.1	<0.05	1	<0.5	<0.2
1456659	Rock	0.046	43	5	0.11	85	0.002	<20	0.40	0.015	0.26	0.6	<0.01	3.6	<0.1	<0.05	1	<0.5	<0.2
1456660	Rock	0.056	29	12	0.29	84	0.010	<20	0.82	0.007	0.52	0.2	<0.01	8.1	0.2	<0.05	2	<0.5	<0.2
1456661	Rock	0.050	43	6	0.10	89	0.003	<20	0.45	0.009	0.39	0.5	<0.01	2.8	0.1	<0.05	1	<0.5	<0.2
1456662	Rock	0.049	49	5	0.13	98	0.002	<20	0.50	0.006	0.37	0.4	<0.01	1.9	0.1	<0.05	1	<0.5	<0.2
1456663	Rock	0.050	46	5	0.15	308	0.001	<20	0.50	0.002	0.35	0.6	<0.01	1.9	<0.1	<0.05	1	<0.5	<0.2
1456664	Rock	0.049	51	5	0.15	154	0.002	<20	0.50	0.007	0.32	0.6	0.02	3.1	<0.1	<0.05	1	<0.5	<0.2
1456665	Rock	0.047	48	5	0.19	70	0.003	<20	0.44	0.008	0.34	0.7	0.01	2.2	0.1	<0.05	1	<0.5	<0.2
1456666	Rock	0.064	26	83	0.58	153	0.010	<20	0.90	0.010	0.48	0.6	0.01	9.3	0.1	0.07	3	<0.5	<0.2
1456667	Rock	0.049	46	8	0.43	220	0.003	<20	0.55	0.006	0.28	1.2	0.01	3.3	<0.1	<0.05	2	<0.5	<0.2
1456668	Rock	0.053	49	6	0.48	39	0.002	<20	0.44	0.006	0.33	1.0	<0.01	2.8	<0.1	0.07	1	0.5	<0.2
1456669	Rock	0.051	44	6	0.46	35	0.003	<20	0.35	0.004	0.30	1.1	0.01	2.9	<0.1	0.11	1	0.5	<0.2
1456670	Rock Pulp	0.059	5	32	0.74	103	0.138	<20	1.58	0.086	0.12	10.2	0.04	5.2	<0.1	<0.05	5	<0.5	<0.2
1456671	Rock	0.053	49	5	0.10	38	0.002	<20	0.43	0.003	0.30	1.0	0.03	2.4	<0.1	<0.05	1	<0.5	0.3
1456672	Rock	0.047	30	4	0.09	38	<0.001	<20	0.57	0.002	0.28	0.3	0.06	1.7	<0.1	0.20	1	0.8	0.3



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 5 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456673	Rock	1.91	0.427	2.1	11.2	21.3	32	0.6	6.0	11.4	431	2.50	183.5	414.1	12.7	32	0.3	0.5	0.3	7	1.07
1456674	Rock	2.17	0.118	1.3	22.6	13.8	51	0.4	3.8	8.3	503	2.51	67.8	115.2	15.0	51	0.1	0.3	0.2	14	1.02
1456675	Rock	2.11	0.173	1.3	16.2	14.9	51	0.8	4.0	9.2	312	2.79	166.4	185.1	16.0	41	<0.1	0.4	0.5	13	0.56
1456676	Rock	2.12	0.111	1.7	14.3	15.8	55	0.4	3.8	9.0	563	2.90	137.2	116.5	14.7	46	0.1	0.4	0.2	15	1.19
1456677	Rock	1.94	0.134	1.4	18.2	8.5	40	0.3	3.2	6.7	406	2.03	128.3	129.4	15.3	52	<0.1	0.4	<0.1	14	1.17
1456678	Rock	2.15	0.453	1.3	15.8	14.2	26	0.8	5.1	10.4	641	2.56	293.5	456.3	14.3	45	0.1	0.8	0.1	18	1.45
1456679	Rock	2.24	0.332	2.2	17.7	13.3	31	0.8	4.8	11.4	961	2.72	215.4	336.1	14.7	34	0.1	0.7	0.3	22	1.09
1456680	Rock	0.21	<0.005	0.1	1.5	2.9	14	<0.1	1.8	1.2	220	0.44	1.0	3.7	0.3	53	<0.1	<0.1	<0.1	<2	21.05
1456681	Rock	2.17	0.350	1.9	18.9	15.1	36	0.9	4.3	11.2	1138	3.08	190.6	351.2	12.5	57	0.3	0.5	0.5	25	2.51
1456682	Rock	2.33	0.040	1.8	5.9	8.2	49	<0.1	3.4	6.4	594	2.18	20.6	45.2	15.8	22	0.1	<0.1	0.1	14	0.76
1456683	Rock	1.79	0.021	1.1	9.4	8.8	64	<0.1	4.0	7.1	369	2.49	9.6	28.0	16.0	42	<0.1	<0.1	0.1	15	0.92
1456684	Rock	2.20	0.016	1.0	4.5	6.3	65	<0.1	3.4	6.3	462	2.33	5.7	16.2	17.1	50	<0.1	<0.1	<0.1	13	0.91
1456685	Rock	2.20	<0.005	1.4	4.7	7.3	56	<0.1	3.4	6.4	698	2.31	3.5	7.2	16.3	54	0.2	<0.1	<0.1	11	1.57
1456686	Rock	2.37	<0.005	1.2	5.1	8.3	52	<0.1	5.7	5.5	519	1.98	2.5	2.7	16.0	66	0.2	<0.1	<0.1	11	1.43
1456687	Rock	2.33	0.039	2.0	6.5	6.4	59	<0.1	4.4	7.0	475	2.44	10.9	39.2	17.0	61	<0.1	<0.1	<0.1	14	1.18
1456688	Rock	2.56	<0.005	1.2	8.0	6.0	49	<0.1	3.4	6.5	493	2.11	2.2	3.0	16.4	32	<0.1	0.1	<0.1	14	0.87
1456689	Rock	2.24	<0.005	1.3	15.3	9.1	52	<0.1	3.2	7.0	386	2.15	2.1	1.6	17.5	30	<0.1	<0.1	<0.1	11	0.74
1456690	Rock	1.94	<0.005	1.6	15.2	8.7	49	<0.1	3.1	6.9	450	2.12	1.6	0.5	17.1	33	<0.1	<0.1	<0.1	11	0.81
1456691	Rock	2.14	0.061	1.2	14.9	31.3	50	0.3	3.5	6.8	271	2.04	64.9	60.6	15.2	26	0.2	0.2	0.7	14	0.57
1456692	Rock	2.34	0.021	1.3	8.2	20.5	60	<0.1	3.9	6.7	317	2.17	19.4	20.0	15.4	35	0.2	0.1	0.2	14	0.68
1456693	Rock	1.99	<0.005	1.5	4.9	28.3	32	<0.1	2.2	3.3	350	1.12	9.2	1.3	10.7	31	0.2	0.2	0.1	15	0.83
1456694	Rock	2.14	<0.005	2.1	1.7	30.2	19	<0.1	1.8	1.9	497	0.75	46.4	1.6	3.9	26	0.3	0.2	0.2	13	0.76
1456695	Rock	2.28	<0.005	1.9	1.4	19.4	16	<0.1	1.9	1.6	418	0.73	44.5	1.2	3.3	21	0.2	0.2	<0.1	14	0.32
1456696	Rock	2.20	<0.005	2.0	2.4	23.3	32	<0.1	2.3	2.6	442	1.16	36.5	1.3	7.8	25	0.3	0.2	0.1	20	0.57
1456697	Rock	2.05	0.007	2.8	2.0	32.8	24	<0.1	2.4	2.0	609	0.97	25.1	6.8	5.1	22	0.5	0.2	0.2	16	0.22
1456698	Rock	2.41	<0.005	1.6	7.2	29.8	69	<0.1	3.9	6.7	512	2.35	16.6	2.4	13.2	39	0.2	0.2	0.2	28	0.97
1456699	Rock	2.05	<0.005	1.6	4.6	19.8	29	<0.1	2.1	3.1	571	1.35	7.1	0.9	10.2	41	0.3	0.3	0.1	24	1.17
1456700	Rock Pulp	0.12	0.823	4.4	34.9	5.3	49	0.3	25.0	9.6	405	2.53	7.1	592.1	0.9	42	0.2	0.8	0.1	59	0.83
1456701	Rock	2.50	<0.005	1.3	14.0	15.1	67	<0.1	4.2	7.9	453	2.72	15.4	0.7	15.4	38	0.2	0.1	0.1	30	0.82
1456702	Rock	2.23	0.029	1.5	14.5	20.3	58	0.1	4.3	9.3	663	2.76	65.0	26.7	19.3	54	0.3	0.3	0.2	37	1.28



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456673	Rock	0.049	27	7	0.37	99	<0.001	<20	0.36	0.003	0.24	2.9	0.05	2.8	<0.1	1.88	<1	1.1	1.4
1456674	Rock	0.050	42	7	0.41	359	0.002	<20	0.59	0.004	0.27	1.3	0.05	2.8	<0.1	0.65	2	0.6	0.5
1456675	Rock	0.050	45	7	0.26	330	0.002	<20	0.69	0.005	0.28	1.1	0.07	2.7	<0.1	0.82	2	1.2	1.1
1456676	Rock	0.050	43	7	0.38	105	0.001	<20	0.64	0.007	0.26	1.0	0.05	4.2	<0.1	0.85	2	1.2	0.5
1456677	Rock	0.053	43	7	0.36	123	0.002	<20	0.52	0.007	0.34	1.1	0.04	3.2	0.1	0.81	2	<0.5	0.4
1456678	Rock	0.055	42	7	0.40	80	0.001	<20	0.30	0.005	0.25	1.8	0.05	5.2	0.2	1.40	<1	1.2	1.6
1456679	Rock	0.052	46	8	0.19	116	0.001	<20	0.36	0.005	0.25	1.0	0.05	5.9	0.1	0.57	1	0.9	1.4
1456680	Rock	0.017	<1	<1	10.16	99	0.002	<20	0.12	0.002	0.10	<0.1	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2
1456681	Rock	0.042	43	8	0.67	52	0.001	<20	0.30	0.006	0.23	1.4	0.05	7.7	<0.1	1.16	<1	1.2	1.9
1456682	Rock	0.049	38	7	0.19	87	0.006	<20	0.71	0.012	0.33	0.5	<0.01	3.6	0.1	<0.05	3	<0.5	<0.2
1456683	Rock	0.050	35	9	0.37	101	0.007	<20	0.81	0.020	0.32	0.5	<0.01	3.7	<0.1	0.22	3	<0.5	<0.2
1456684	Rock	0.055	45	8	0.33	68	0.005	<20	0.70	0.014	0.33	0.6	<0.01	3.5	<0.1	0.10	3	<0.5	<0.2
1456685	Rock	0.055	43	8	0.48	61	0.006	<20	0.60	0.008	0.30	0.4	<0.01	4.5	<0.1	0.14	2	<0.5	<0.2
1456686	Rock	0.053	45	11	0.20	79	0.004	<20	0.57	0.009	0.27	0.4	<0.01	4.0	<0.1	0.07	2	<0.5	<0.2
1456687	Rock	0.049	39	8	0.34	148	0.019	<20	0.79	0.010	0.38	0.7	<0.01	3.0	0.1	0.17	3	<0.5	<0.2
1456688	Rock	0.052	41	8	0.33	99	0.033	<20	0.73	0.014	0.49	0.4	<0.01	2.7	0.2	0.09	3	<0.5	<0.2
1456689	Rock	0.053	47	7	0.30	71	0.016	<20	0.80	0.014	0.40	0.5	<0.01	2.5	0.1	0.17	3	0.5	<0.2
1456690	Rock	0.054	47	7	0.28	75	0.017	<20	0.74	0.014	0.42	0.5	<0.01	2.4	0.1	0.19	3	<0.5	<0.2
1456691	Rock	0.049	34	7	0.32	54	0.012	<20	0.81	0.010	0.36	0.6	0.02	2.5	0.1	0.40	3	0.9	0.4
1456692	Rock	0.048	40	7	0.32	46	0.011	<20	0.89	0.012	0.40	0.6	0.01	2.2	0.1	0.13	3	0.5	<0.2
1456693	Rock	0.022	25	9	0.12	56	0.011	<20	0.39	0.025	0.18	1.2	0.01	1.5	<0.1	<0.05	2	<0.5	<0.2
1456694	Rock	0.010	12	10	0.03	67	0.003	<20	0.18	0.037	0.10	1.2	0.02	1.0	0.2	<0.05	<1	<0.5	<0.2
1456695	Rock	0.010	12	9	0.02	83	0.005	<20	0.18	0.040	0.10	1.4	0.04	0.8	0.1	<0.05	<1	<0.5	<0.2
1456696	Rock	0.012	23	10	0.08	60	0.006	<20	0.37	0.033	0.13	1.0	0.03	1.3	<0.1	<0.05	2	<0.5	<0.2
1456697	Rock	0.011	13	10	0.03	87	0.005	<20	0.19	0.034	0.10	1.3	0.01	1.2	<0.1	<0.05	<1	<0.5	<0.2
1456698	Rock	0.044	34	10	0.24	77	0.016	<20	0.71	0.024	0.22	1.3	0.01	4.0	0.2	0.06	3	<0.5	<0.2
1456699	Rock	0.025	27	9	0.15	60	0.012	<20	0.30	0.034	0.15	1.6	<0.01	2.2	<0.1	0.08	1	<0.5	<0.2
1456700	Rock Pulp	0.057	5	32	0.73	98	0.129	<20	1.53	0.085	0.13	11.7	0.04	4.8	<0.1	<0.05	5	<0.5	<0.2
1456701	Rock	0.058	46	10	0.39	234	0.022	<20	0.93	0.030	0.29	1.1	0.02	4.6	0.1	0.19	4	<0.5	<0.2
1456702	Rock	0.066	52	10	0.47	118	0.022	<20	0.87	0.026	0.29	1.1	0.05	5.3	0.1	0.47	5	<0.5	0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 6 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456703	Rock	2.41	0.010	1.5	3.6	15.6	69	<0.1	3.8	6.9	635	2.46	28.3	8.2	16.2	60	0.1	0.2	<0.1	23	1.23
1456704	Rock	2.27	<0.005	1.8	2.0	21.2	19	0.1	2.3	2.2	429	0.90	23.8	1.6	3.5	51	<0.1	0.1	0.3	17	1.02
1456705	Rock	2.24	<0.005	1.5	1.8	19.7	19	<0.1	2.0	1.6	389	0.69	15.1	0.9	2.1	43	<0.1	<0.1	0.2	14	1.08
1456706	Rock	1.99	<0.005	1.7	1.9	26.8	16	0.1	1.9	1.3	301	0.68	16.1	<0.5	2.9	55	<0.1	0.1	0.5	19	0.95
1456707	Rock	1.99	0.008	1.6	2.0	37.5	19	0.2	2.0	1.2	214	0.75	15.4	4.6	3.4	37	0.2	<0.1	0.9	21	0.67
1456708	Rock	2.09	0.010	1.6	1.9	35.1	22	0.2	2.0	1.5	255	0.76	13.8	4.3	3.3	40	0.3	0.1	0.7	22	0.70
1456709	Rock	2.07	0.018	1.5	2.3	34.5	19	0.3	2.1	1.5	257	0.77	15.8	15.9	3.6	41	0.2	0.1	0.8	19	0.75
1456710	Rock	0.24	<0.005	0.1	1.6	2.9	15	<0.1	1.6	1.0	217	0.44	0.9	<0.5	0.2	48	<0.1	0.1	<0.1	2	18.41
1456711	Rock	1.94	<0.005	1.7	2.7	31.0	14	<0.1	1.7	1.3	185	0.78	7.1	1.7	2.2	57	0.1	0.2	0.3	25	0.52
1456712	Rock	1.96	<0.005	1.5	1.4	24.8	17	<0.1	1.5	1.1	231	0.75	5.0	1.7	1.9	57	0.2	0.2	0.3	26	0.77
1456713	Rock	1.90	0.025	1.8	2.8	37.7	16	0.2	2.1	1.6	180	0.72	43.0	20.7	3.7	44	0.2	0.3	0.8	15	0.69
1456714	Rock	1.80	0.010	2.0	2.0	27.0	15	0.1	1.6	1.3	222	0.77	5.3	8.7	3.0	64	0.2	0.2	0.5	26	0.97
1456715	Rock	1.98	0.007	1.9	7.8	17.9	55	<0.1	3.4	6.6	463	2.22	13.2	12.6	13.5	56	0.1	0.2	0.1	22	1.19
1456716	Rock	1.59	0.007	2.3	28.2	8.9	63	0.1	23.4	9.7	399	2.56	9.1	1.8	4.5	51	0.3	0.6	0.2	52	1.19
1456717	Rock	2.10	0.011	1.9	12.1	7.1	51	<0.1	7.2	7.6	577	2.35	5.4	4.2	13.8	35	0.2	0.2	0.2	23	1.33
1456718	Rock	2.69	<0.005	1.3	8.2	13.2	53	<0.1	4.1	6.6	660	2.09	1.6	1.4	17.4	84	0.2	<0.1	0.2	16	1.68
1456719	Rock	2.20	<0.005	0.9	6.9	12.6	56	<0.1	4.0	7.0	552	2.53	1.3	<0.5	20.2	36	<0.1	<0.1	0.1	26	0.83
1456720	Rock	0.15	0.006	0.2	3.2	2.9	19	<0.1	2.0	1.1	222	0.49	1.6	<0.5	0.5	50	<0.1	0.2	<0.1	3	17.81



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000420.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	1	0.5	0.2	
1456703	Rock	0.057	52	9	0.45	50	0.005	<20	0.85	0.021	0.24	0.7	0.02	4.4	<0.1	0.13	4	<0.5	<0.2
1456704	Rock	0.016	12	10	0.15	169	0.004	<20	0.26	0.039	0.12	1.9	0.01	1.3	<0.1	0.08	1	<0.5	<0.2
1456705	Rock	0.011	7	10	0.13	65	0.002	<20	0.20	0.036	0.10	2.0	0.01	1.1	<0.1	<0.05	1	<0.5	<0.2
1456706	Rock	0.012	10	10	0.12	85	0.004	<20	0.16	0.039	0.10	2.1	0.01	1.0	<0.1	0.06	<1	<0.5	<0.2
1456707	Rock	0.012	10	10	0.10	43	0.004	<20	0.14	0.041	0.10	2.1	0.01	0.8	<0.1	0.09	<1	<0.5	<0.2
1456708	Rock	0.011	9	11	0.16	64	0.004	<20	0.14	0.044	0.10	4.0	<0.01	0.7	<0.1	0.13	<1	<0.5	<0.2
1456709	Rock	0.011	9	10	0.15	49	0.004	<20	0.15	0.046	0.11	4.2	<0.01	0.8	<0.1	0.14	<1	<0.5	<0.2
1456710	Rock	0.017	<1	<1	12.20	78	0.002	<20	0.05	0.002	0.03	0.1	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1456711	Rock	0.009	7	11	0.11	162	0.010	<20	0.17	0.058	0.13	4.4	0.02	0.8	<0.1	<0.05	<1	<0.5	<0.2
1456712	Rock	0.012	8	10	0.13	229	0.007	<20	0.16	0.043	0.10	3.1	<0.01	0.9	<0.1	<0.05	<1	<0.5	<0.2
1456713	Rock	0.012	8	11	0.14	99	0.003	<20	0.15	0.048	0.11	5.4	<0.01	0.7	<0.1	0.20	<1	<0.5	0.2
1456714	Rock	0.011	9	11	0.13	113	0.008	<20	0.15	0.049	0.11	4.7	0.02	0.8	<0.1	<0.05	<1	<0.5	<0.2
1456715	Rock	0.049	41	10	0.35	90	0.029	<20	0.86	0.025	0.39	1.4	0.02	2.7	0.1	0.09	4	<0.5	<0.2
1456716	Rock	0.087	17	28	0.62	325	0.076	<20	1.16	0.043	0.13	1.0	0.02	4.3	<0.1	<0.05	4	<0.5	<0.2
1456717	Rock	0.051	32	9	0.21	168	0.016	<20	0.55	0.029	0.21	1.0	0.01	3.0	<0.1	<0.05	2	<0.5	<0.2
1456718	Rock	0.046	37	7	0.16	94	0.007	<20	0.46	0.023	0.19	1.1	<0.01	3.2	<0.1	0.09	3	<0.5	<0.2
1456719	Rock	0.051	50	8	0.51	80	0.077	<20	0.94	0.030	0.56	0.4	<0.01	4.6	0.2	<0.05	5	<0.5	<0.2
1456720	Rock	0.017	1	1	11.68	140	0.002	<20	0.07	0.002	0.04	0.1	<0.01	0.4	<0.1	<0.05	<1	<0.5	<0.2



QUALITY CONTROL REPORT

WHI16000420.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
REP 1456592	QC		0.7	55.8	16.4	61	<0.1	60.1	24.0	699	3.92	2.4	<0.5	6.7	187	<0.1	0.1	0.1	99	5.35	
1456621	Rock	2.34	0.006	5.5	6.0	23.5	37	<0.1	1.0	2.7	478	1.95	19.8	4.9	7.3	106	<0.1	1.7	0.2	6	1.68
REP 1456621	QC		0.009																		
1456623	Rock	2.28	<0.005	3.2	5.7	8.4	40	<0.1	1.1	3.3	577	2.05	24.0	4.5	9.3	66	<0.1	1.6	0.2	5	1.21
REP 1456623	QC		<0.005																		
REP 1456626	QC		1.5	3.1	4.9	42	<0.1	1.7	3.5	621	1.87	7.9	1.1	20.0	43	<0.1	0.5	0.2	7	0.82	
1456661	Rock	2.19	<0.005	1.7	5.4	17.5	33	<0.1	3.4	6.2	557	2.07	1.2	0.6	15.6	49	0.1	<0.1	0.2	15	1.95
REP 1456661	QC		1.7	5.5	17.8	34	<0.1	3.4	6.4	564	2.09	1.1	0.8	15.8	50	0.1	<0.1	0.2	15	1.95	
1456695	Rock	2.28	<0.005	1.9	1.4	19.4	16	<0.1	1.9	1.6	418	0.73	44.5	1.2	3.3	21	0.2	0.2	<0.1	14	0.32
REP 1456695	QC		<0.005																		
1456696	Rock	2.20	<0.005	2.0	2.4	23.3	32	<0.1	2.3	2.6	442	1.16	36.5	1.3	7.8	25	0.3	0.2	0.1	20	0.57
REP 1456696	QC		1.8	2.1	22.3	31	<0.1	2.3	2.7	430	1.12	36.8	2.2	7.3	24	0.2	0.2	0.1	20	0.54	
1456697	Rock	2.05	0.007	2.8	2.0	32.8	24	<0.1	2.4	2.0	609	0.97	25.1	6.8	5.1	22	0.5	0.2	0.2	16	0.22
REP 1456697	QC		0.007																		
Core Reject Duplicates																					
1456592	Rock	3.08	<0.005	0.9	57.7	17.0	63	<0.1	64.2	25.1	718	4.00	2.4	1.0	6.6	190	<0.1	0.1	0.1	102	5.38
DUP 1456592	QC	<0.01	<0.005	0.7	56.3	16.8	59	<0.1	60.4	23.8	699	3.91	2.6	<0.5	6.7	185	<0.1	0.1	0.1	99	5.36
1456626	Rock	2.33	<0.005	1.6	3.1	4.9	41	<0.1	1.8	3.7	605	1.83	7.5	2.9	20.0	42	<0.1	0.5	0.2	7	0.80
DUP 1456626	QC	<0.01	<0.005	1.5	3.1	4.8	42	<0.1	1.7	3.5	608	1.85	7.7	1.0	19.8	41	<0.1	0.5	0.2	7	0.80
1456660	Rock	2.36	<0.005	1.4	5.0	18.2	49	<0.1	6.9	9.8	682	2.48	1.9	<0.5	10.9	27	0.2	<0.1	0.2	34	1.82
DUP 1456660	QC	<0.01	<0.005	1.5	5.3	18.4	50	<0.1	7.3	10.1	696	2.54	2.0	<0.5	10.8	27	0.2	<0.1	0.2	35	1.86
1456694	Rock	2.14	<0.005	2.1	1.7	30.2	19	<0.1	1.8	1.9	497	0.75	46.4	1.6	3.9	26	0.3	0.2	0.2	13	0.76
DUP 1456694	QC	<0.01	<0.005	2.0	1.6	29.9	18	<0.1	1.7	1.9	499	0.76	46.2	1.9	4.0	26	0.1	0.2	0.2	13	0.73
Reference Materials																					
STD DS10	Standard		13.2	154.1	148.2	362	1.8	72.5	12.4	885	2.78	46.2	69.3	7.9	74	2.7	9.9	13.6	41	1.06	
STD DS10	Standard		13.7	156.6	149.9	371	2.0	76.0	12.9	900	2.79	46.6	69.9	7.7	73	2.6	7.8	13.1	42	1.07	
STD DS10	Standard		14.8	157.8	146.5	360	1.9	74.0	12.8	896	2.78	49.7	85.5	7.8	68	2.7	8.4	13.6	44	1.06	
STD DS10	Standard		13.6	158.5	145.9	353	1.7	75.7	13.0	881	2.72	48.6	107.1	7.2	69	2.5	8.2	12.5	41	1.04	



QUALITY CONTROL REPORT

WHI16000420.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
REP 1456592	QC	0.182	25	142	2.49	771	0.333	<20	2.44	0.035	2.05	0.3	<0.01	8.6	0.5	<0.05	10	<0.5	<0.2
1456621	Rock	0.019	10	5	0.29	1668	<0.001	<20	0.28	0.013	0.16	0.4	0.22	3.1	<0.1	0.08	<1	<0.5	<0.2
REP 1456621																			
1456623	Rock	0.034	12	6	0.17	429	0.002	<20	0.34	0.022	0.20	0.5	0.13	3.2	<0.1	0.08	1	<0.5	<0.2
REP 1456623																			
REP 1456626	QC	0.033	43	8	0.37	518	0.066	<20	0.74	0.041	0.57	1.1	0.04	2.1	0.3	0.12	4	<0.5	<0.2
1456661	Rock	0.050	43	6	0.10	89	0.003	<20	0.45	0.009	0.39	0.5	<0.01	2.8	0.1	<0.05	1	<0.5	<0.2
REP 1456661	QC	0.052	43	6	0.10	92	0.003	<20	0.46	0.009	0.39	0.5	<0.01	2.6	0.1	<0.05	1	<0.5	<0.2
1456695	Rock	0.010	12	9	0.02	83	0.005	<20	0.18	0.040	0.10	1.4	0.04	0.8	0.1	<0.05	<1	<0.5	<0.2
REP 1456695																			
1456696	Rock	0.012	23	10	0.08	60	0.006	<20	0.37	0.033	0.13	1.0	0.03	1.3	<0.1	<0.05	2	<0.5	<0.2
REP 1456696	QC	0.011	21	10	0.08	59	0.005	<20	0.36	0.033	0.12	1.0	0.03	1.2	<0.1	<0.05	2	<0.5	<0.2
1456697	Rock	0.011	13	10	0.03	87	0.005	<20	0.19	0.034	0.10	1.3	0.01	1.2	<0.1	<0.05	<1	<0.5	<0.2
REP 1456697																			
Core Reject Duplicates																			
1456592	Rock	0.191	26	147	2.58	795	0.332	<20	2.48	0.035	2.11	0.2	<0.01	8.8	0.6	<0.05	11	<0.5	<0.2
DUP 1456592	QC	0.177	25	140	2.45	770	0.324	<20	2.40	0.034	2.01	0.2	<0.01	8.6	0.5	<0.05	11	<0.5	<0.2
1456626	Rock	0.033	40	8	0.36	511	0.065	<20	0.72	0.039	0.55	1.2	0.03	2.2	0.2	0.12	4	<0.5	<0.2
DUP 1456626	QC	0.033	41	8	0.37	514	0.065	<20	0.73	0.040	0.56	1.1	0.04	2.2	0.3	0.12	4	<0.5	<0.2
1456660	Rock	0.056	29	12	0.29	84	0.010	<20	0.82	0.007	0.52	0.2	<0.01	8.1	0.2	<0.05	2	<0.5	<0.2
DUP 1456660	QC	0.059	28	12	0.29	86	0.010	<20	0.83	0.007	0.53	0.2	<0.01	8.0	0.2	<0.05	2	<0.5	<0.2
1456694	Rock	0.010	12	10	0.03	67	0.003	<20	0.18	0.037	0.10	1.2	0.02	1.0	0.2	<0.05	<1	<0.5	<0.2
DUP 1456694	QC	0.010	12	10	0.03	69	0.003	<20	0.18	0.040	0.10	1.2	0.02	1.0	0.2	<0.05	<1	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.078	19	54	0.78	425	0.083	<20	1.05	0.072	0.34	2.7	0.28	3.2	5.1	0.27	4	1.9	5.0
STD DS10	Standard	0.080	19	56	0.79	441	0.085	<20	1.08	0.073	0.34	3.0	0.27	3.2	5.3	0.28	4	2.3	4.7
STD DS10	Standard	0.079	18	56	0.77	420	0.080	<20	1.03	0.069	0.33	2.8	0.27	3.0	5.1	0.28	4	2.1	5.5
STD DS10	Standard	0.079	18	55	0.77	424	0.079	<20	1.03	0.071	0.34	3.1	0.25	3.0	5.1	0.27	4	2.0	4.6



QUALITY CONTROL REPORT

WHI16000420.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OREAS45EA	Standard			1.6	701.8	15.4	32	0.3	389.4	53.0	420	23.61	11.7	58.1	11.4	5	<0.1	0.3	0.3	320	0.03
STD OREAS45EA	Standard			1.5	709.2	15.0	33	0.3	388.4	54.7	426	23.51	12.3	64.2	11.0	4	<0.1	0.3	0.3	321	0.03
STD OREAS45EA	Standard			1.6	721.2	15.4	33	0.3	401.6	56.0	432	23.16	12.2	54.2	10.9	4	<0.1	0.4	0.3	309	0.03
STD OREAS45EA	Standard			1.6	709.8	15.4	32	0.3	391.1	56.5	430	23.95	11.8	55.4	10.8	4	<0.1	0.3	0.3	325	0.03
STD OXD108	Standard		0.420																		
STD OXD108	Standard		0.405																		
STD OXD108	Standard		0.423																		
STD OXI121	Standard		1.892																		
STD OXI121	Standard		1.832																		
STD OXI121	Standard		1.823																		
STD OXN117	Standard		7.675																		
STD OXN117	Standard		7.821																		
STD OXN117	Standard		7.448																		
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash				<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 2 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000420.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OREAS45EA	Standard	0.031	8	827	0.10	156	0.108	<20	3.20	0.018	0.05	<0.1	<0.01	88.1	<0.1	<0.05	13	0.8	<0.2	
STD OREAS45EA	Standard	0.032	8	879	0.10	153	0.109	<20	3.20	0.018	0.05	<0.1	0.01	87.2	<0.1	<0.05	13	1.4	<0.2	
STD OREAS45EA	Standard	0.035	8	870	0.11	153	0.105	<20	3.41	0.026	0.06	<0.1	0.01	87.8	<0.1	<0.05	14	1.1	<0.2	
STD OREAS45EA	Standard	0.033	8	878	0.10	152	0.107	<20	3.16	0.018	0.05	<0.1	0.02	85.9	<0.1	<0.05	13	1.2	<0.2	
STD OXD108	Standard																			
STD OXD108	Standard																			
STD OXD108	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXI121	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXD108 Expected																				
STD OXN117 Expected																				
STD OXI121 Expected																				
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
Prep Wash																				



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000420.1

WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca		
kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%		
0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01		
ROCK-WHI	Prep Blank	<0.005	0.6	3.2	1.3	29	<0.1	0.5	3.1	398	1.59	0.7	<0.5	2.3	26	<0.1	<0.1	<0.1	21	0.59	
ROCK-WHI	Prep Blank	<0.005	0.7	3.8	1.4	32	<0.1	0.9	3.5	415	1.72	0.9	<0.5	2.4	29	<0.1	<0.1	<0.1	23	0.62	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 20, 2016

Page: 3 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000420.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
ROCK-WHI	Prep Blank	0.040	5	2	0.38	69	0.083	<20	0.98	0.125	0.12	0.1	<0.01	2.5	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.045	5	2	0.39	68	0.086	<20	0.97	0.113	0.10	0.1	0.04	2.9	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 02, 2016
Report Date: November 22, 2016
Page: 1 of 6

CERTIFICATE OF ANALYSIS

WHI16000421.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV-10-30-2016 RAB
P.O. Number
Number of Samples: 138

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	138	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	138	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	138	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	138	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	138	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 2 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456721	Rock	2.36	<0.005	0.9	7.2	14.3	51	<0.1	3.5	7.0	511	2.20	1.5	0.8	19.1	37	0.1	<0.1	0.2	23	0.89
1456722	Rock	2.00	<0.005	1.2	8.0	6.8	56	<0.1	3.5	7.0	591	2.47	3.9	4.4	20.1	31	<0.1	<0.1	<0.1	27	0.89
1456723	Rock	2.50	<0.005	1.1	7.9	6.9	55	<0.1	4.0	7.6	542	2.36	1.6	0.9	21.2	32	<0.1	<0.1	<0.1	24	0.67
1456724	Rock	2.45	<0.005	0.9	6.1	7.7	54	<0.1	3.2	6.9	547	2.33	1.9	<0.5	19.6	36	<0.1	<0.1	<0.1	23	0.95
1456725	Rock	2.23	<0.005	1.0	7.1	6.9	66	<0.1	4.1	8.4	626	2.74	1.4	<0.5	21.7	43	<0.1	<0.1	<0.1	27	0.97
1456726	Rock	2.09	<0.005	0.9	10.1	20.5	57	<0.1	3.5	7.1	528	2.35	1.5	<0.5	20.2	47	0.1	<0.1	0.3	25	0.87
1456727	Rock	2.15	<0.005	1.8	13.0	7.8	54	<0.1	3.7	7.4	543	2.34	1.7	<0.5	19.1	62	<0.1	<0.1	<0.1	21	1.22
1456728	Rock	2.37	<0.005	0.8	6.6	5.5	54	<0.1	3.1	6.3	549	2.31	1.2	<0.5	14.7	77	<0.1	<0.1	<0.1	23	1.40
1456729	Rock	1.87	<0.005	1.3	11.5	13.2	54	<0.1	3.3	6.4	479	2.17	1.6	<0.5	19.1	118	0.1	<0.1	0.1	23	1.66
1456730	Rock	2.35	<0.005	1.2	11.1	14.7	53	<0.1	3.3	6.7	480	2.19	1.6	<0.5	19.1	119	0.1	<0.1	0.2	23	1.66
1456731	Rock	2.45	0.009	1.5	10.2	13.9	45	<0.1	3.0	6.0	553	2.04	1.4	<0.5	18.5	101	0.1	<0.1	0.2	21	2.12
1456732	Rock	1.97	<0.005	1.1	7.6	10.1	60	<0.1	3.5	6.8	470	2.21	1.1	<0.5	19.0	52	<0.1	<0.1	0.1	19	0.91
1456733	Rock	2.02	<0.005	1.6	6.0	5.2	49	<0.1	3.4	7.3	509	2.33	1.4	<0.5	19.9	63	<0.1	<0.1	<0.1	19	1.21
1456734	Rock	2.27	<0.005	1.3	7.1	5.7	55	<0.1	3.7	7.2	577	2.40	1.8	<0.5	21.8	85	<0.1	<0.1	<0.1	22	1.40
1456735	Rock	2.17	<0.005	1.2	12.4	6.0	51	<0.1	4.2	6.6	503	2.22	1.2	<0.5	20.8	67	<0.1	<0.1	<0.1	19	1.33
1456736	Rock	2.36	<0.005	1.0	4.4	7.1	53	<0.1	3.8	7.6	541	2.43	2.4	<0.5	21.3	69	<0.1	<0.1	<0.1	19	1.52
1456737	Rock	2.13	<0.005	1.4	14.4	93.0	92	0.3	3.5	7.0	509	2.35	1.7	<0.5	17.4	87	1.8	<0.1	1.3	20	1.60
1456738	Rock	2.30	<0.005	1.3	5.3	7.4	56	<0.1	3.3	6.9	514	2.29	2.2	<0.5	18.4	80	<0.1	<0.1	0.1	20	1.56
1456739	Rock	2.34	0.007	1.9	11.0	24.0	58	0.2	3.5	7.4	603	2.45	2.6	5.1	19.9	71	<0.1	<0.1	0.5	25	1.60
1456740	Rock Pulp	0.12	2.334	66.7	2244.8	1332.7	3680	28.1	184.0	21.1	621	5.39	1157.4	2092.2	2.7	74	21.6	16.6	10.9	57	1.47
1456741	Rock	2.07	<0.005	1.2	9.2	8.0	57	<0.1	3.4	6.8	405	2.10	1.3	<0.5	21.7	61	<0.1	<0.1	<0.1	17	1.03
1456742	Rock	2.02	0.079	197.7	17.5	41.9	52	0.9	5.7	11.8	689	2.86	27.5	80.3	16.8	70	0.7	0.3	2.6	15	2.62
1456743	Rock	1.87	0.179	120.8	24.1	59.8	80	2.5	4.2	8.8	750	3.07	65.0	163.6	17.8	65	1.2	0.3	4.0	19	2.51
1456744	Rock	1.58	0.042	14.9	12.5	21.0	51	0.4	3.2	6.5	612	2.26	18.9	39.2	19.2	63	0.2	<0.1	0.6	17	1.56
1456745	Rock	1.30	0.031	9.9	13.5	15.3	46	0.2	3.0	6.5	506	1.98	9.9	46.6	19.2	50	0.2	<0.1	0.3	17	1.26
1456746	Rock	1.78	0.012	3.2	17.5	18.5	61	0.1	15.8	10.6	605	2.50	6.3	11.7	15.5	78	0.2	<0.1	0.2	21	1.93
1456747	Rock	1.19	0.007	2.4	24.9	13.1	55	<0.1	10.5	8.9	607	2.50	2.4	6.4	18.0	83	0.2	<0.1	0.2	23	2.14
1456748	Rock	2.14	0.005	3.4	8.7	10.4	57	<0.1	6.3	8.3	570	2.53	2.4	3.8	21.4	66	<0.1	<0.1	0.1	22	1.52
1456749	Rock	1.40	0.016	2.7	8.1	8.1	54	<0.1	5.5	8.1	595	2.50	2.4	4.1	21.8	71	<0.1	<0.1	0.1	21	1.73
1456750	Rock Pulp	0.12	<0.005	2.6	29.1	2.7	45	0.5	25.0	10.7	414	2.50	4.9	<0.5	1.0	40	0.2	0.3	<0.1	61	0.81



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 2 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Ti ppm	S %	Ga ppm	Se ppm	Te ppm	
1456721	Rock	0.041	44	7	0.45	115	0.083	<20	0.84	0.026	0.59	0.4	<0.01	3.4	0.2	<0.05	5	<0.5	<0.2
1456722	Rock	0.044	48	8	0.57	125	0.099	<20	0.94	0.029	0.62	0.5	<0.01	4.0	0.2	<0.05	5	<0.5	<0.2
1456723	Rock	0.045	52	8	0.49	170	0.089	<20	0.91	0.032	0.62	0.4	<0.01	3.3	0.3	<0.05	5	<0.5	<0.2
1456724	Rock	0.040	51	8	0.51	115	0.079	<20	0.88	0.029	0.54	0.4	<0.01	3.3	0.2	0.05	5	<0.5	<0.2
1456725	Rock	0.052	55	10	0.66	185	0.107	<20	1.08	0.034	0.66	0.3	<0.01	4.7	0.2	<0.05	7	<0.5	<0.2
1456726	Rock	0.043	49	8	0.55	124	0.094	<20	0.94	0.034	0.57	0.4	<0.01	4.0	0.2	<0.05	5	<0.5	<0.2
1456727	Rock	0.044	48	9	0.49	145	0.054	<20	0.80	0.037	0.39	0.4	<0.01	3.9	0.2	0.10	5	<0.5	<0.2
1456728	Rock	0.050	42	7	0.47	113	0.056	<20	0.82	0.037	0.41	0.5	<0.01	3.9	0.2	0.06	5	<0.5	<0.2
1456729	Rock	0.047	47	7	0.38	109	0.035	<20	0.70	0.034	0.31	0.5	<0.01	3.9	0.1	0.10	4	<0.5	<0.2
1456730	Rock	0.046	49	7	0.38	117	0.036	<20	0.72	0.034	0.32	0.5	<0.01	3.9	0.2	0.10	5	<0.5	<0.2
1456731	Rock	0.038	46	8	0.36	184	0.038	<20	0.61	0.029	0.29	0.7	<0.01	4.0	0.1	0.10	4	<0.5	<0.2
1456732	Rock	0.039	47	9	0.47	102	0.060	<20	0.79	0.038	0.43	0.6	<0.01	3.3	0.2	0.07	5	<0.5	<0.2
1456733	Rock	0.040	51	9	0.47	109	0.052	<20	0.81	0.035	0.42	0.4	<0.01	3.4	0.2	0.10	5	<0.5	<0.2
1456734	Rock	0.047	49	9	0.52	104	0.071	<20	1.02	0.030	0.58	0.3	<0.01	3.3	0.2	<0.05	6	<0.5	<0.2
1456735	Rock	0.045	43	8	0.43	131	0.065	<20	0.81	0.028	0.50	0.4	<0.01	3.6	0.2	0.08	4	<0.5	<0.2
1456736	Rock	0.049	49	8	0.49	103	0.036	<20	0.83	0.027	0.37	0.2	<0.01	3.5	0.1	<0.05	5	<0.5	<0.2
1456737	Rock	0.046	46	9	0.43	144	0.041	<20	0.75	0.033	0.36	0.3	<0.01	3.7	0.2	0.14	5	<0.5	<0.2
1456738	Rock	0.047	45	8	0.46	139	0.023	<20	0.79	0.032	0.30	0.2	<0.01	3.7	0.1	0.06	5	<0.5	<0.2
1456739	Rock	0.045	45	10	0.49	127	0.071	<20	0.79	0.035	0.46	0.7	<0.01	4.4	0.1	0.23	5	<0.5	<0.2
1456740	Rock Pulp	0.063	11	45	0.86	151	0.084	<20	1.47	0.081	0.19	7.9	0.70	4.4	1.3	1.53	6	3.3	0.6
1456741	Rock	0.047	35	8	0.41	58	0.040	<20	0.85	0.028	0.45	0.3	<0.01	4.3	0.2	0.11	4	<0.5	<0.2
1456742	Rock	0.044	25	7	0.92	166	0.008	<20	0.48	0.021	0.28	0.7	0.11	3.4	0.3	1.38	2	0.7	0.6
1456743	Rock	0.045	21	8	0.97	56	0.001	<20	0.31	0.022	0.24	0.9	0.05	4.4	<0.1	1.96	<1	1.4	2.1
1456744	Rock	0.046	30	8	0.55	81	0.004	<20	0.38	0.027	0.25	0.8	<0.01	3.9	<0.1	0.41	2	<0.5	0.3
1456745	Rock	0.042	29	7	0.47	67	0.008	<20	0.39	0.021	0.27	0.7	0.01	4.3	<0.1	0.31	2	<0.5	<0.2
1456746	Rock	0.042	25	30	0.67	78	0.007	<20	0.55	0.027	0.30	0.7	<0.01	7.0	<0.1	0.65	2	<0.5	<0.2
1456747	Rock	0.042	41	25	0.52	88	0.025	<20	0.66	0.034	0.33	0.5	<0.01	5.3	0.1	0.31	4	<0.5	<0.2
1456748	Rock	0.041	46	17	0.55	111	0.058	<20	0.84	0.033	0.51	0.4	<0.01	4.1	0.2	0.12	5	<0.5	<0.2
1456749	Rock	0.043	50	15	0.52	123	0.033	<20	0.78	0.030	0.36	0.2	<0.01	4.3	0.1	0.10	5	<0.5	<0.2
1456750	Rock Pulp	0.062	5	33	0.80	98	0.128	<20	1.55	0.083	0.14	12.1	<0.01	4.6	<0.1	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 3 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456751	Rock	2.06	0.011	3.1	11.9	9.4	56	<0.1	4.8	8.2	652	2.63	2.5	3.6	17.8	101	0.1	<0.1	0.1	25	2.29
1456752	Rock	1.12	0.005	3.0	7.0	6.7	46	<0.1	4.6	6.8	515	2.23	1.9	1.2	15.6	68	<0.1	<0.1	0.1	19	1.46
1456753	Rock	1.34	<0.005	1.3	6.4	5.4	43	<0.1	3.6	6.3	472	1.96	1.3	<0.5	13.2	62	<0.1	<0.1	0.1	16	1.33
1456754	Rock	1.71	0.056	7.6	25.0	42.9	70	0.3	16.0	10.9	467	2.56	19.1	69.8	10.6	47	0.4	0.3	0.7	39	0.49
1456755	Rock	2.14	0.021	3.4	19.7	15.1	49	0.2	12.7	6.8	397	1.87	10.8	17.2	6.7	45	0.3	0.3	0.3	30	0.98
1456756	Rock	3.07	0.046	5.8	25.6	19.8	40	0.3	3.7	3.2	349	1.35	10.0	48.8	5.9	24	0.3	0.2	0.5	17	0.07
1456757	Rock	1.96	0.150	4.0	25.0	24.3	64	0.5	4.1	5.1	467	2.22	35.9	160.4	10.3	24	0.9	0.2	0.6	18	0.10
1456758	Rock	2.15	0.099	4.8	18.7	27.7	57	0.3	5.3	6.9	592	2.14	18.8	99.6	18.0	22	0.4	0.1	0.6	22	0.18
1456759	Rock	1.81	0.245	9.3	33.1	36.4	65	0.8	7.6	7.8	362	3.36	43.4	293.8	21.7	30	0.7	0.2	1.2	19	0.13
1456760	Rock	2.06	0.231	8.3	37.5	33.9	60	0.8	6.5	7.1	323	3.10	37.0	217.1	20.4	29	0.7	0.2	1.0	21	0.13
1456761	Rock	2.13	0.365	23.3	24.7	47.9	67	1.0	10.3	12.0	453	3.79	57.0	328.6	20.3	31	1.0	0.3	2.3	7	0.06
1456762	Rock	2.10	0.194	40.1	25.2	66.0	61	0.8	13.5	10.0	447	4.00	60.5	186.0	17.3	41	0.6	0.3	5.0	10	0.06
1456763	Rock	2.07	0.167	21.7	28.0	37.9	56	0.8	7.0	9.2	522	3.47	41.4	182.1	17.5	36	0.3	0.3	1.6	8	0.07
1456764	Rock	2.06	0.206	30.9	25.4	39.4	65	0.6	6.5	9.3	647	4.24	54.1	214.2	18.3	32	0.5	0.3	1.3	8	0.06
1456765	Rock	2.19	0.219	82.5	19.5	49.9	39	0.8	5.7	9.2	382	3.51	51.4	218.4	18.7	33	0.2	0.3	3.5	11	0.08
1456766	Rock	2.25	0.125	8.1	16.1	19.5	32	0.5	3.8	7.6	430	2.26	24.9	132.2	18.3	29	0.2	0.1	0.6	12	0.18
1456767	Rock	2.25	0.182	2.1	12.9	15.0	41	0.7	3.8	8.0	379	2.31	24.1	190.2	17.7	45	0.2	0.2	0.3	13	1.11
1456768	Rock	2.03	0.462	7.4	25.9	41.6	50	2.0	5.6	11.3	575	3.62	71.4	453.5	18.1	49	0.3	0.5	1.0	13	1.75
1456769	Rock	1.96	0.158	2.1	12.2	13.8	46	0.5	3.2	8.1	465	2.21	21.2	126.4	20.1	54	0.1	0.1	0.2	13	1.17
1456770	Rock Pulp	0.12	0.829	4.0	33.4	5.4	52	0.3	24.0	9.3	397	2.50	6.4	777.7	0.9	40	0.3	0.8	0.1	60	0.80
1456771	Rock	1.96	0.075	2.9	16.1	63.8	55	0.7	3.5	6.9	653	2.26	19.4	69.4	18.4	59	0.3	0.1	1.4	17	1.41
1456772	Rock	2.84	0.015	2.2	11.4	12.6	55	0.1	3.6	7.0	494	2.29	5.9	10.6	19.6	63	0.2	0.1	0.2	19	1.37
1456773	Rock	2.65	0.026	2.4	8.0	6.3	56	<0.1	3.8	7.6	513	2.51	9.5	23.9	17.8	41	<0.1	<0.1	0.1	22	0.92
1456774	Rock	2.57	0.129	1.9	10.6	17.7	58	0.6	3.9	7.9	519	2.52	45.4	127.4	17.2	65	0.3	0.2	0.3	14	1.63
1456775	Rock	2.80	0.110	11.7	14.0	24.1	55	0.5	4.8	9.7	1633	2.95	38.7	106.3	16.3	78	0.4	0.2	0.8	17	2.00
1456776	Rock	3.03	0.136	4.3	9.0	13.8	60	0.5	10.0	7.5	634	2.43	41.2	155.3	18.3	56	0.1	0.2	0.3	14	0.97
1456777	Rock	2.26	0.090	3.8	10.0	16.4	42	0.3	4.7	7.2	832	2.18	20.9	71.2	15.0	70	0.2	0.1	0.3	16	2.22
1456778	Rock	2.59	0.046	3.7	6.2	7.1	43	0.2	3.6	4.6	399	1.79	14.0	47.6	15.5	38	0.1	<0.1	0.1	12	0.62
1456779	Rock	2.01	0.068	7.1	14.2	10.8	41	0.4	5.6	6.5	723	2.03	19.4	69.6	16.1	36	0.1	0.2	0.4	14	0.58
1456780	Rock Pulp	0.12	<0.005	2.5	24.4	2.5	46	0.3	22.7	9.9	411	2.47	4.6	<0.5	1.0	42	0.2	0.3	<0.1	61	0.81



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 3 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1456751	Rock	0.053	45	17	0.54	264	0.030	<20	0.77	0.036	0.37	0.4	<0.01	4.3	0.1	0.14	4	<0.5	<0.2
1456752	Rock	0.038	40	14	0.44	114	0.029	<20	0.65	0.031	0.32	0.2	<0.01	3.8	0.1	0.09	4	<0.5	<0.2
1456753	Rock	0.033	36	7	0.39	76	0.020	<20	0.59	0.030	0.26	<0.1	<0.01	3.4	<0.1	0.05	4	<0.5	<0.2
1456754	Rock	0.056	28	24	0.47	246	0.046	<20	0.89	0.022	0.28	3.5	0.02	5.6	0.1	<0.05	3	<0.5	0.3
1456755	Rock	0.048	20	13	0.37	216	0.039	<20	0.64	0.027	0.16	2.9	0.02	2.9	<0.1	<0.05	2	<0.5	<0.2
1456756	Rock	0.006	27	5	0.06	184	0.010	<20	0.33	0.012	0.14	2.5	0.04	1.5	<0.1	<0.05	1	<0.5	0.3
1456757	Rock	0.022	22	4	0.05	318	0.005	<20	0.27	0.009	0.16	1.0	0.08	3.3	<0.1	<0.05	<1	<0.5	0.7
1456758	Rock	0.055	42	6	0.13	170	0.012	<20	0.55	0.013	0.31	0.5	0.05	4.4	0.1	<0.05	2	<0.5	0.7
1456759	Rock	0.046	43	6	0.10	135	0.014	<20	0.56	0.006	0.21	0.3	0.09	4.5	<0.1	<0.05	2	<0.5	1.3
1456760	Rock	0.045	40	6	0.09	118	0.012	<20	0.50	0.005	0.20	0.3	0.09	4.3	<0.1	<0.05	2	<0.5	1.2
1456761	Rock	0.042	44	4	0.03	133	0.005	<20	0.23	0.005	0.18	0.3	0.12	1.2	<0.1	0.07	<1	<0.5	2.5
1456762	Rock	0.035	56	6	0.05	149	0.006	<20	0.37	0.005	0.25	0.2	0.11	1.8	<0.1	0.17	1	<0.5	2.3
1456763	Rock	0.049	49	4	0.04	220	0.002	<20	0.26	0.005	0.23	0.2	0.08	2.1	<0.1	0.11	<1	<0.5	2.1
1456764	Rock	0.041	59	3	0.03	346	0.002	<20	0.22	0.004	0.20	0.3	0.07	1.6	<0.1	0.08	<1	<0.5	2.5
1456765	Rock	0.048	60	4	0.04	102	0.001	<20	0.26	0.003	0.20	0.3	0.10	4.2	<0.1	<0.05	<1	<0.5	1.7
1456766	Rock	0.046	41	4	0.07	121	0.002	<20	0.40	0.008	0.26	0.3	0.04	3.5	<0.1	0.10	1	<0.5	0.9
1456767	Rock	0.050	33	5	0.30	63	0.006	<20	0.45	0.015	0.28	1.0	0.05	2.6	<0.1	0.80	2	<0.5	1.5
1456768	Rock	0.057	47	5	0.29	111	0.002	<20	0.28	0.008	0.22	0.7	0.08	3.1	<0.1	1.12	<1	0.7	3.6
1456769	Rock	0.046	40	5	0.18	79	0.003	<20	0.39	0.015	0.24	1.0	0.03	3.2	<0.1	0.51	1	<0.5	0.8
1456770	Rock Pulp	0.059	5	31	0.74	97	0.124	<20	1.50	0.086	0.14	10.5	0.04	4.7	<0.1	<0.05	5	<0.5	<0.2
1456771	Rock	0.049	41	5	0.30	135	0.004	<20	0.40	0.018	0.28	1.0	0.03	4.0	0.1	0.40	2	<0.5	0.3
1456772	Rock	0.051	50	7	0.29	82	0.020	<20	0.60	0.023	0.32	0.8	0.01	3.4	0.1	0.20	4	<0.5	<0.2
1456773	Rock	0.052	47	7	0.38	100	0.042	<20	0.79	0.024	0.44	0.4	<0.01	3.7	0.2	0.13	4	<0.5	<0.2
1456774	Rock	0.052	37	6	0.46	62	0.010	<20	0.51	0.019	0.32	0.6	0.02	3.5	0.1	0.71	2	<0.5	1.0
1456775	Rock	0.053	36	5	0.35	314	0.003	<20	0.42	0.015	0.27	0.6	0.05	6.1	<0.1	0.51	2	<0.5	0.8
1456776	Rock	0.051	38	8	0.30	118	0.004	<20	0.46	0.014	0.27	0.2	0.04	4.8	<0.1	0.37	2	<0.5	0.9
1456777	Rock	0.042	34	5	0.52	82	0.004	<20	0.41	0.023	0.25	0.2	0.03	4.5	<0.1	0.51	2	<0.5	0.7
1456778	Rock	0.043	38	3	0.13	55	0.006	<20	0.43	0.018	0.25	0.1	0.01	2.8	<0.1	0.11	2	<0.5	0.3
1456779	Rock	0.048	44	5	0.18	121	0.015	<20	0.47	0.021	0.31	<0.1	0.02	3.7	0.1	0.19	2	<0.5	0.9
1456780	Rock Pulp	0.058	4	30	0.80	97	0.124	<20	1.56	0.083	0.14	12.2	0.01	5.0	<0.1	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 4 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456781	Rock	1.20	0.015	1.9	16.2	7.2	43	<0.1	12.8	7.7	302	1.64	7.7	10.2	5.2	78	0.2	0.3	0.2	28	1.11
1456782	Rock	1.85	0.032	2.1	15.5	15.5	53	0.1	9.7	7.8	550	2.34	6.8	30.2	15.0	28	0.3	0.2	0.5	30	0.49
1456783	Rock	1.71	0.066	2.4	16.8	37.5	65	0.2	8.1	10.1	1163	2.57	10.1	39.8	23.1	18	0.3	0.1	0.6	27	0.20
1456784	Rock	1.36	0.041	1.7	17.2	36.0	67	0.1	7.5	7.6	447	2.74	11.4	49.9	22.8	16	0.3	<0.1	0.5	25	0.17
1456785	Rock	1.83	0.034	1.5	15.8	20.4	66	0.1	5.8	7.3	448	2.72	10.8	32.0	22.9	15	0.2	0.1	0.4	24	0.17
1456786	Rock	1.77	0.050	2.2	24.1	31.0	65	0.2	7.2	7.3	327	2.74	12.8	55.6	23.7	17	0.2	0.1	0.8	27	0.17
1456787	Rock	1.46	0.071	1.8	26.7	41.0	60	0.2	6.5	6.9	280	2.82	16.2	60.4	20.8	16	0.3	0.1	1.2	26	0.15
1456788	Rock	1.80	0.079	2.6	20.7	23.1	70	0.3	7.9	8.8	403	2.97	17.3	84.9	21.9	20	0.2	0.2	0.6	28	0.19
1456789	Rock	1.48	0.077	2.3	25.5	24.8	73	0.3	10.3	9.2	503	3.11	18.2	75.9	29.9	24	0.3	0.2	0.5	29	0.23
1456790	Rock	1.81	0.076	2.3	27.0	24.9	73	0.3	10.6	9.3	474	3.05	18.8	70.3	30.0	24	0.3	0.2	0.5	29	0.22
1456791	Rock	1.05	0.085	4.9	24.6	28.0	68	0.3	9.2	9.1	569	2.70	19.7	62.1	24.5	17	0.3	0.1	0.5	21	0.15
1456792	Rock	1.50	0.023	2.0	15.9	13.7	60	0.1	6.5	7.8	493	2.47	6.5	20.6	24.7	18	0.1	0.1	0.3	23	0.18
1456793	Rock	1.27	0.016	1.5	16.8	23.7	65	0.1	5.4	7.1	369	2.47	3.8	9.5	20.6	16	0.1	<0.1	0.3	23	0.17
1456794	Rock	1.93	0.012	1.5	13.0	13.5	75	<0.1	5.3	10.8	561	2.66	3.4	4.5	20.3	19	0.2	<0.1	0.2	24	0.21
1456795	Rock	1.50	0.012	1.7	16.7	76.8	64	0.1	4.8	7.7	545	2.41	3.4	3.3	19.3	18	0.2	0.1	1.1	24	0.19
1456796	Rock	1.80	0.021	2.0	17.7	39.3	63	0.3	4.6	7.1	349	2.39	5.5	19.7	18.7	19	0.2	<0.1	0.9	22	0.19
1456797	Rock	1.90	0.023	2.1	15.0	54.4	70	0.2	6.5	7.6	403	2.57	5.1	10.1	21.6	17	0.2	<0.1	0.3	24	0.19
1456798	Rock	1.69	0.020	2.2	12.2	46.4	65	0.1	5.5	6.8	323	2.62	6.4	16.5	23.0	16	0.3	<0.1	0.3	21	0.20
1456799	Rock	1.48	0.087	3.5	19.8	24.9	59	0.3	6.3	7.4	338	2.86	24.3	100.2	21.9	17	0.2	0.1	0.4	19	0.20
1456800	Rock Pulp	0.13	2.555	66.0	2204.9	1302.2	3604	26.1	184.0	20.4	627	5.30	1198.5	2435.2	2.8	85	20.7	16.5	10.2	55	1.47
1456801	Rock	1.71	0.057	4.1	21.2	15.8	64	0.2	5.0	9.1	1291	2.71	12.8	109.9	10.5	25	0.3	0.1	0.3	32	0.38
1456802	Rock	1.65	0.029	3.6	13.8	14.8	55	0.2	4.6	9.1	1236	2.39	10.7	29.8	16.3	19	0.2	<0.1	0.3	22	0.23
1456803	Rock	1.61	0.020	1.9	9.2	10.9	58	<0.1	3.9	5.4	327	2.10	7.5	16.7	17.9	15	0.2	<0.1	0.2	17	0.19
1456804	Rock	1.77	0.009	2.7	16.5	9.1	61	<0.1	4.0	7.3	389	2.54	5.8	10.3	21.1	17	0.2	<0.1	0.2	20	0.22
1456805	Rock	1.74	0.015	1.5	10.9	40.0	68	<0.1	4.1	5.7	254	2.19	4.7	9.6	17.1	20	0.1	<0.1	0.6	21	0.27
1456806	Rock	1.58	0.010	2.3	9.1	12.3	58	<0.1	4.1	6.3	373	2.29	6.4	18.8	19.8	17	0.1	0.1	0.2	19	0.21
1456807	Rock	1.53	0.010	3.3	17.2	35.1	60	<0.1	4.2	7.8	433	2.45	6.5	8.6	21.7	18	0.3	0.1	0.8	20	0.21
1456808	Rock	1.44	0.006	3.4	21.3	19.8	76	<0.1	3.9	8.2	470	2.80	4.5	0.8	22.6	23	0.2	<0.1	0.4	24	0.25
1456809	Rock	1.57	0.007	2.4	12.0	13.0	69	<0.1	4.6	8.0	337	2.63	2.6	1.7	23.6	19	0.2	<0.1	0.2	23	0.25
1456810	Rock Pulp	0.13	0.751	4.0	34.3	6.0	50	0.3	24.6	9.3	400	2.53	7.1	456.5	1.0	45	0.3	1.0	0.1	61	0.85



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 4 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Ti ppm	S %	Ga ppm	Se ppm	Te ppm	
1456781	Rock	0.055	17	14	0.35	196	0.039	<20	0.68	0.027	0.14	4.6	0.02	2.5	<0.1	0.13	2	0.8	<0.2
1456782	Rock	0.055	31	12	0.28	224	0.036	<20	0.88	0.027	0.26	2.1	0.04	4.7	<0.1	<0.05	3	<0.5	<0.2
1456783	Rock	0.049	43	12	0.19	354	0.022	<20	0.94	0.016	0.32	2.7	0.02	5.7	0.1	<0.05	4	<0.5	<0.2
1456784	Rock	0.046	40	9	0.18	102	0.016	<20	0.99	0.013	0.33	0.5	0.02	5.9	0.1	<0.05	4	<0.5	0.2
1456785	Rock	0.047	39	8	0.20	97	0.021	<20	0.97	0.014	0.36	0.3	0.02	5.9	0.1	<0.05	4	<0.5	<0.2
1456786	Rock	0.045	47	9	0.22	108	0.024	<20	1.10	0.013	0.35	0.3	0.04	6.6	0.1	<0.05	4	<0.5	<0.2
1456787	Rock	0.045	48	9	0.18	83	0.024	<20	1.06	0.011	0.30	0.2	0.03	5.9	0.1	<0.05	4	<0.5	0.3
1456788	Rock	0.056	50	12	0.26	141	0.025	<20	1.24	0.011	0.36	0.3	0.05	7.0	0.1	<0.05	5	<0.5	0.3
1456789	Rock	0.052	63	14	0.32	184	0.034	<20	1.64	0.016	0.48	0.2	0.04	8.0	0.2	<0.05	6	<0.5	0.4
1456790	Rock	0.052	64	14	0.31	159	0.034	<20	1.64	0.015	0.47	0.1	0.04	8.0	0.1	<0.05	6	<0.5	0.4
1456791	Rock	0.048	55	9	0.15	156	0.017	<20	0.96	0.008	0.30	0.2	0.04	6.0	0.2	<0.05	3	<0.5	0.5
1456792	Rock	0.046	52	9	0.38	138	0.067	<20	1.27	0.014	0.59	0.3	0.01	5.8	0.2	<0.05	5	<0.5	<0.2
1456793	Rock	0.043	44	9	0.33	198	0.058	<20	1.07	0.019	0.48	0.5	0.01	6.3	0.2	<0.05	5	<0.5	<0.2
1456794	Rock	0.048	43	9	0.46	195	0.062	<20	1.20	0.023	0.52	0.5	0.01	6.2	0.1	<0.05	5	<0.5	<0.2
1456795	Rock	0.045	39	8	0.26	152	0.033	<20	0.94	0.022	0.37	0.6	<0.01	5.4	<0.1	<0.05	4	<0.5	<0.2
1456796	Rock	0.043	40	8	0.23	164	0.024	<20	0.96	0.018	0.35	0.4	0.01	5.0	0.1	<0.05	4	<0.5	0.3
1456797	Rock	0.049	49	10	0.28	128	0.045	<20	1.08	0.020	0.45	0.4	0.02	5.5	0.1	<0.05	5	<0.5	<0.2
1456798	Rock	0.049	52	9	0.19	105	0.021	<20	0.96	0.016	0.34	0.3	0.01	5.3	0.1	<0.05	4	<0.5	<0.2
1456799	Rock	0.050	52	8	0.15	145	0.012	<20	0.90	0.010	0.32	0.3	0.03	5.2	<0.1	<0.05	3	<0.5	1.4
1456800	Rock Pulp	0.063	12	45	0.87	239	0.095	<20	1.50	0.080	0.19	8.1	0.67	4.9	1.3	1.49	6	4.4	0.5
1456801	Rock	0.111	48	7	0.19	360	0.012	<20	1.08	0.019	0.33	0.4	0.02	6.1	<0.1	<0.05	4	<0.5	0.2
1456802	Rock	0.061	49	7	0.15	326	0.015	<20	0.80	0.017	0.27	0.4	0.02	5.2	<0.1	<0.05	3	<0.5	<0.2
1456803	Rock	0.045	36	7	0.17	99	0.020	<20	0.73	0.014	0.29	0.3	0.03	4.6	<0.1	<0.05	3	<0.5	<0.2
1456804	Rock	0.053	45	9	0.21	97	0.019	<20	0.77	0.014	0.32	0.5	0.01	4.3	0.1	<0.05	4	<0.5	<0.2
1456805	Rock	0.063	35	7	0.24	72	0.022	<20	0.91	0.017	0.35	0.5	0.03	4.8	0.1	<0.05	4	<0.5	<0.2
1456806	Rock	0.049	36	8	0.22	98	0.027	<20	0.72	0.014	0.37	0.5	<0.01	4.8	0.1	<0.05	4	<0.5	<0.2
1456807	Rock	0.048	47	8	0.22	87	0.027	<20	0.66	0.018	0.32	0.5	0.03	4.9	0.1	<0.05	4	<0.5	<0.2
1456808	Rock	0.052	61	9	0.29	92	0.024	<20	0.73	0.024	0.24	1.1	<0.01	5.8	<0.1	<0.05	5	<0.5	<0.2
1456809	Rock	0.053	59	10	0.36	94	0.053	<20	0.82	0.020	0.44	0.5	<0.01	4.4	0.2	<0.05	5	<0.5	<0.2
1456810	Rock Pulp	0.058	5	33	0.77	104	0.139	<20	1.55	0.088	0.14	10.5	0.04	5.2	<0.1	<0.05	5	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 5 of 6

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456811	Rock	2.12	0.016	2.9	21.3	21.2	71	<0.1	3.7	7.0	844	2.45	4.6	8.8	22.1	100	0.3	<0.1	0.3	22	1.09
1456812	Rock	3.24	0.348	2.6	15.1	31.7	89	2.4	4.0	7.3	600	2.41	30.5	336.3	17.9	68	0.5	0.1	0.3	16	1.39
1456813	Rock	1.79	0.027	3.0	8.7	20.5	63	0.1	3.5	7.4	684	2.47	6.5	31.9	18.1	60	0.2	<0.1	0.2	17	1.09
1456814	Rock	3.08	0.006	1.8	7.6	9.9	63	<0.1	3.6	6.5	467	2.38	4.3	14.4	21.4	65	0.1	<0.1	<0.1	18	1.04
1456815	Rock	1.69	0.007	1.3	6.6	9.5	57	<0.1	3.7	7.1	561	2.38	3.0	5.1	20.4	73	0.1	<0.1	0.1	19	1.33
1456816	Rock	2.03	0.008	1.3	6.1	7.1	59	<0.1	4.4	7.5	609	2.46	2.6	0.7	19.5	65	0.1	<0.1	<0.1	19	1.21
1456817	Rock	2.65	0.011	1.3	6.9	7.1	48	<0.1	3.2	6.2	620	2.19	11.7	6.5	19.9	69	0.2	0.1	0.1	15	1.65
1456818	Rock	2.90	0.009	1.3	6.3	11.5	45	<0.1	2.8	5.7	508	1.97	3.3	1.4	17.6	53	0.1	<0.1	0.2	13	1.18
1456819	Rock	2.81	0.005	1.0	5.0	10.7	56	<0.1	3.8	6.1	597	2.23	2.6	<0.5	18.1	71	0.2	<0.1	0.1	17	1.07
1456820	Rock Pulp	0.12	0.006	2.4	24.4	2.6	45	0.3	22.8	9.7	402	2.45	4.4	<0.5	1.0	44	0.2	0.3	<0.1	60	0.83
1456821	Rock	2.85	0.019	0.9	5.5	16.0	52	<0.1	3.1	6.1	564	2.11	6.1	8.4	17.8	77	0.1	<0.1	0.2	14	1.19
1456822	Rock	2.37	0.053	1.2	5.9	12.5	52	<0.1	3.6	6.3	595	2.17	11.4	43.5	17.6	66	0.1	<0.1	0.1	15	1.31
1456823	Rock	2.27	0.014	1.2	8.8	395.6	112	2.8	3.3	6.8	653	2.34	3.4	11.4	19.5	83	2.1	<0.1	6.5	18	1.93
1456824	Rock	1.98	0.015	1.0	6.0	19.7	46	0.1	3.0	5.8	558	2.01	12.4	10.4	18.6	74	<0.1	<0.1	0.2	13	1.63
1456825	Rock	2.83	0.008	1.2	11.0	15.5	43	<0.1	3.5	5.4	409	1.76	3.9	4.4	16.8	82	<0.1	0.1	0.2	14	1.50
1456826	Rock	2.22	0.045	1.2	8.4	24.7	48	0.2	4.5	6.2	566	2.03	18.2	43.0	18.5	79	0.2	0.1	0.3	16	1.70
1456827	Rock	2.21	0.017	1.5	8.0	8.9	56	<0.1	3.2	5.8	546	2.05	12.7	8.7	14.9	72	0.1	<0.1	<0.1	15	1.46
1456828	Rock	1.78	0.016	1.4	8.3	28.1	45	0.1	2.7	5.1	532	1.84	11.5	13.2	13.2	111	0.2	<0.1	0.3	14	1.89
1456829	Rock	2.19	<0.005	1.4	11.7	11.9	41	<0.1	2.7	5.0	440	1.84	4.0	<0.5	15.8	78	0.2	<0.1	0.2	16	1.43
1456830	Rock	1.93	0.005	1.4	10.0	11.3	41	<0.1	2.7	4.9	432	1.83	3.7	<0.5	16.1	78	0.1	<0.1	0.2	16	1.41
1456831	Rock	3.85	<0.005	1.3	12.6	7.6	57	<0.1	3.4	6.3	486	2.23	3.6	<0.5	16.9	77	0.1	<0.1	0.1	18	1.55
1456832	Rock	1.12	0.007	1.3	10.6	10.1	43	<0.1	2.4	4.1	386	1.54	3.5	<0.5	10.8	79	<0.1	<0.1	0.1	13	1.28
1456833	Rock	2.42	<0.005	0.7	10.1	9.4	50	<0.1	3.8	5.5	445	1.84	4.1	1.5	10.5	105	<0.1	0.1	0.1	15	1.74
1456834	Rock	2.06	0.028	0.8	20.4	45.6	73	0.2	4.8	6.5	586	2.37	9.4	19.5	21.0	15	0.3	0.1	0.8	28	0.21
1456835	Rock	2.14	0.012	0.6	12.7	11.9	46	0.1	3.5	5.5	469	1.90	2.3	4.8	16.1	101	0.2	<0.1	0.2	20	0.73
1456836	Rock	2.37	<0.005	0.6	9.7	7.6	48	<0.1	3.2	5.7	416	1.98	1.8	1.0	15.5	37	0.2	<0.1	0.2	20	0.64
1456837	Rock	2.21	0.006	0.5	7.3	60.5	57	0.2	3.2	5.5	430	1.81	1.4	<0.5	14.0	72	0.4	<0.1	1.1	20	0.95
1456838	Rock	2.43	<0.005	0.5	8.4	11.7	53	<0.1	11.4	6.4	480	2.03	2.3	<0.5	14.6	50	0.1	<0.1	0.3	23	0.94
1456839	Rock	2.25	<0.005	0.6	3.4	6.7	55	<0.1	3.4	6.9	521	2.22	1.7	<0.5	18.4	44	<0.1	<0.1	<0.1	22	0.91
1456840	Rock Pulp	0.13	2.386	61.3	2186.9	1263.7	3622	25.1	188.7	20.0	627	5.30	1206.7	1364.6	2.7	88	21.0	17.5	11.1	55	1.49



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 5 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456811	Rock	0.051	53	9	0.32	158	0.040	<20	0.63	0.025	0.33	0.9	<0.01	5.7	0.1	0.07	3	<0.5	<0.2
1456812	Rock	0.050	42	8	0.36	216	0.011	<20	0.42	0.017	0.25	1.4	0.02	4.6	<0.1	0.64	2	0.5	4.0
1456813	Rock	0.048	46	7	0.32	146	0.010	<20	0.48	0.017	0.23	0.8	<0.01	4.5	<0.1	0.09	3	<0.5	<0.2
1456814	Rock	0.053	50	9	0.32	290	0.017	<20	0.60	0.024	0.22	0.3	<0.01	5.4	<0.1	<0.05	3	<0.5	<0.2
1456815	Rock	0.050	50	9	0.48	140	0.033	<20	0.71	0.021	0.31	0.4	<0.01	4.2	0.1	<0.05	4	<0.5	<0.2
1456816	Rock	0.051	52	10	0.50	88	0.041	<20	0.71	0.030	0.37	0.5	<0.01	4.7	0.1	0.07	4	<0.5	<0.2
1456817	Rock	0.048	52	9	0.31	113	0.020	<20	0.41	0.030	0.26	0.8	<0.01	4.7	<0.1	0.13	2	<0.5	<0.2
1456818	Rock	0.046	44	8	0.26	112	0.005	<20	0.32	0.022	0.22	0.6	0.01	3.8	<0.1	0.15	2	<0.5	<0.2
1456819	Rock	0.048	32	10	0.30	81	0.004	<20	0.39	0.022	0.22	0.5	<0.01	5.6	<0.1	<0.05	2	<0.5	<0.2
1456820	Rock Pulp	0.061	5	30	0.81	99	0.132	<20	1.56	0.081	0.14	12.2	0.03	5.0	<0.1	<0.05	5	<0.5	<0.2
1456821	Rock	0.043	25	7	0.33	64	0.004	<20	0.39	0.021	0.22	0.4	<0.01	4.7	<0.1	0.13	2	<0.5	<0.2
1456822	Rock	0.049	30	8	0.33	93	0.008	<20	0.39	0.017	0.26	0.5	0.01	4.6	<0.1	0.21	2	<0.5	<0.2
1456823	Rock	0.049	39	9	0.62	104	0.028	<20	0.50	0.021	0.31	1.1	0.03	4.5	<0.1	0.29	3	1.4	<0.2
1456824	Rock	0.048	31	6	0.35	70	0.007	<20	0.33	0.017	0.23	1.0	<0.01	4.0	<0.1	0.21	1	<0.5	<0.2
1456825	Rock	0.055	20	9	0.29	65	0.014	<20	0.54	0.022	0.27	0.4	<0.01	4.4	<0.1	0.09	3	<0.5	<0.2
1456826	Rock	0.057	42	11	0.39	60	0.018	<20	0.47	0.021	0.24	0.9	<0.01	5.5	<0.1	0.27	2	<0.5	0.3
1456827	Rock	0.045	32	8	0.44	48	0.014	<20	0.43	0.020	0.23	0.9	<0.01	4.1	<0.1	0.08	2	<0.5	<0.2
1456828	Rock	0.045	25	8	0.36	81	0.015	<20	0.44	0.018	0.25	1.0	<0.01	4.3	<0.1	0.19	2	<0.5	<0.2
1456829	Rock	0.049	25	8	0.29	69	0.017	<20	0.47	0.020	0.27	0.5	<0.01	4.2	<0.1	0.09	3	<0.5	<0.2
1456830	Rock	0.049	25	9	0.29	72	0.018	<20	0.46	0.020	0.27	0.5	<0.01	4.2	<0.1	0.08	3	<0.5	<0.2
1456831	Rock	0.052	41	10	0.40	100	0.013	<20	0.55	0.026	0.21	0.5	<0.01	4.8	<0.1	0.12	4	<0.5	<0.2
1456832	Rock	0.030	22	8	0.30	85	0.014	<20	0.40	0.023	0.20	0.3	<0.01	3.6	<0.1	0.11	2	<0.5	<0.2
1456833	Rock	0.043	25	6	0.42	88	0.007	<20	0.57	0.018	0.23	<0.1	<0.01	3.8	<0.1	0.17	3	<0.5	<0.2
1456834	Rock	0.051	67	7	0.23	181	0.007	<20	0.80	0.017	0.15	0.4	0.03	5.6	<0.1	<0.05	5	<0.5	<0.2
1456835	Rock	0.038	44	6	0.36	97	0.026	<20	0.60	0.016	0.17	0.9	0.01	3.5	<0.1	<0.05	4	<0.5	<0.2
1456836	Rock	0.036	43	6	0.42	100	0.059	<20	0.72	0.022	0.34	0.7	0.01	2.9	0.2	<0.05	4	<0.5	<0.2
1456837	Rock	0.040	41	6	0.40	110	0.056	<20	0.70	0.015	0.29	0.7	<0.01	2.4	0.2	<0.05	4	<0.5	<0.2
1456838	Rock	0.057	39	23	0.53	115	0.070	<20	0.81	0.020	0.36	0.4	<0.01	3.3	0.2	<0.05	5	<0.5	<0.2
1456839	Rock	0.044	44	6	0.52	111	0.084	<20	0.94	0.018	0.47	0.4	<0.01	1.9	0.2	<0.05	5	<0.5	<0.2
1456840	Rock Pulp	0.066	12	44	0.87	267	0.092	<20	1.49	0.079	0.19	8.3	0.74	4.7	1.3	1.51	6	4.4	0.6

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 6 of 6 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456841	Rock	2.18	<0.005	0.5	5.5	18.6	62	<0.1	3.2	6.5	529	2.11	1.6	1.0	19.9	78	0.1	0.3	0.3	23	1.18
1456842	Rock	2.00	0.006	0.6	19.0	16.8	65	<0.1	3.4	7.4	595	2.45	1.9	2.6	17.7	59	0.1	<0.1	0.5	24	1.15
1456843	Rock	1.94	0.006	0.6	7.6	9.8	58	<0.1	3.4	6.9	522	2.34	1.7	0.7	17.9	45	<0.1	<0.1	0.1	24	0.85
1456844	Rock	2.20	<0.005	0.7	11.8	6.4	64	<0.1	4.1	7.9	517	2.47	1.4	<0.5	18.0	60	<0.1	<0.1	<0.1	31	0.94
1456845	Rock	2.86	0.030	0.8	9.5	11.2	62	<0.1	3.4	7.1	673	2.40	7.0	23.2	17.6	90	<0.1	0.2	0.1	31	1.48
1456846	Rock	2.93	0.079	0.8	14.2	12.1	56	0.1	3.3	6.5	476	2.27	10.0	46.9	19.0	66	0.2	0.1	0.2	24	1.08
1456847	Rock	1.84	0.091	1.0	7.9	13.0	62	0.1	3.5	7.7	683	2.51	9.5	32.6	17.9	76	0.1	0.1	0.2	24	1.63
1456848	Rock	1.24	0.028	0.9	12.2	69.5	81	0.2	14.5	10.1	639	2.56	4.0	20.7	11.9	117	0.4	<0.1	1.0	42	3.08
1456849	Rock	1.36	0.017	2.0	16.0	14.0	78	<0.1	14.9	9.8	680	2.72	6.8	13.2	15.4	44	0.2	0.1	0.3	31	1.39
1456850	Rock Pulp	0.12	0.034	2.2	25.1	2.5	45	0.2	23.4	9.8	403	2.44	4.8	<0.5	1.0	44	0.2	0.3	<0.1	59	0.83
1456851	Rock	1.05	0.015	5.4	20.1	58.8	83	0.3	53.4	18.7	1091	3.60	7.6	14.8	10.8	134	0.5	0.2	1.4	56	4.26
1456852	Rock	1.42	0.014	3.2	17.9	25.5	67	0.1	16.9	8.6	602	2.46	6.8	12.4	17.2	78	0.2	0.1	0.6	25	1.91
1456853	Rock	2.76	<0.005	1.6	13.2	9.8	60	<0.1	9.9	8.3	561	2.51	3.8	1.5	19.3	70	0.1	0.2	0.1	25	1.55
1456854	Rock	3.26	0.006	1.5	14.6	9.2	59	<0.1	5.3	7.6	556	2.25	6.5	4.3	9.7	70	0.2	0.1	0.1	32	1.45
1456855	Rock	2.12	<0.005	1.0	16.7	9.0	61	<0.1	5.4	8.8	616	2.70	2.4	<0.5	16.3	106	<0.1	0.2	0.1	34	1.78
1456856	Rock	2.13	<0.005	1.7	15.1	12.9	75	<0.1	15.5	9.6	912	2.83	5.4	1.1	18.7	125	0.4	0.1	0.1	28	2.45
1456857	Rock	1.78	0.028	2.5	18.9	101.9	70	0.4	7.0	6.8	848	2.06	17.9	16.3	16.5	75	0.7	0.1	1.9	21	1.89
1456858	Rock	2.12	0.009	1.3	22.6	54.0	62	0.2	3.9	6.5	550	2.27	2.6	5.1	17.6	107	0.4	0.2	0.9	27	1.43



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 6 of 6

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000421.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1456841	Rock	0.047	40	7	0.48	97	0.061	<20	0.76	0.022	0.26	0.6	<0.01	3.0	0.1	<0.05	5	<0.5	<0.2	
1456842	Rock	0.048	50	7	0.47	105	0.020	<20	0.74	0.018	0.17	0.3	<0.01	3.5	<0.1	<0.05	5	<0.5	<0.2	
1456843	Rock	0.047	46	7	0.54	112	0.080	<20	0.94	0.023	0.47	0.4	<0.01	2.6	0.2	<0.05	5	<0.5	<0.2	
1456844	Rock	0.063	41	10	0.64	126	0.121	<20	1.07	0.030	0.59	0.6	<0.01	2.9	0.3	<0.05	5	<0.5	<0.2	
1456845	Rock	0.042	48	8	0.54	133	0.051	<20	0.77	0.035	0.30	0.8	<0.01	4.8	0.1	<0.05	4	<0.5	<0.2	
1456846	Rock	0.049	53	7	0.35	120	0.010	<20	0.67	0.021	0.15	0.2	<0.01	4.8	<0.1	<0.05	5	<0.5	0.2	
1456847	Rock	0.053	50	8	0.43	149	0.009	<20	0.82	0.020	0.17	0.3	<0.01	5.1	<0.1	<0.05	5	<0.5	0.3	
1456848	Rock	0.061	37	54	0.40	216	0.020	<20	0.99	0.013	0.25	0.3	0.02	8.7	<0.1	<0.05	5	<0.5	<0.2	
1456849	Rock	0.052	37	37	0.55	281	0.055	<20	1.11	0.013	0.55	0.3	<0.01	6.4	0.2	<0.05	5	<0.5	<0.2	
1456850	Rock Pulp	0.061	5	30	0.81	100	0.131	<20	1.56	0.080	0.13	12.7	<0.01	5.0	<0.1	<0.05	5	<0.5	<0.2	
1456851	Rock	0.057	34	141	1.10	348	0.090	<20	1.54	0.012	0.74	0.2	0.02	14.2	0.4	<0.05	6	<0.5	<0.2	
1456852	Rock	0.062	44	35	0.38	312	0.025	<20	0.95	0.014	0.37	0.2	0.02	6.4	0.1	<0.05	4	<0.5	<0.2	
1456853	Rock	0.062	49	20	0.42	217	0.031	<20	0.95	0.027	0.40	0.1	0.01	5.4	0.2	<0.05	5	<0.5	<0.2	
1456854	Rock	0.064	30	12	0.40	272	0.040	<20	0.80	0.038	0.36	0.3	0.02	5.8	0.2	<0.05	5	<0.5	<0.2	
1456855	Rock	0.060	46	11	0.53	232	0.057	<20	0.98	0.029	0.46	0.2	<0.01	5.3	0.2	<0.05	5	<0.5	<0.2	
1456856	Rock	0.061	52	31	0.50	389	0.032	<20	1.03	0.026	0.37	0.3	<0.01	5.9	0.1	<0.05	6	<0.5	<0.2	
1456857	Rock	0.050	41	8	0.22	383	0.006	<20	0.65	0.015	0.26	0.5	<0.01	4.0	<0.1	<0.05	3	<0.5	<0.2	
1456858	Rock	0.045	45	8	0.32	173	0.030	<20	0.70	0.031	0.33	0.3	<0.01	3.9	0.1	<0.05	4	<0.5	<0.2	



QUALITY CONTROL REPORT

WHI16000421.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
REP 1456725	QC		1.0	6.7	6.4	61	<0.1	3.9	7.8	607	2.65	1.5	<0.5	20.2	40	<0.1	<0.1	<0.1	27	0.90	
REP 1456759	QC		9.4	34.9	35.7	65	0.8	7.4	8.0	363	3.40	43.7	357.4	21.6	29	0.7	0.2	1.2	19	0.13	
1456768	Rock	2.03	0.462	7.4	25.9	41.6	50	2.0	5.6	11.3	575	3.62	71.4	453.5	18.1	49	0.3	0.5	1.0	13	1.75
REP 1456768	QC		0.487																		
1456770	Rock Pulp	0.12	0.829	4.0	33.4	5.4	52	0.3	24.0	9.3	397	2.50	6.4	777.7	0.9	40	0.3	0.8	0.1	60	0.80
REP 1456770	QC		0.909																		
REP 1456793	QC		1.6	13.9	24.2	65	0.1	5.9	7.4	385	2.61	4.0	9.0	21.7	17	0.2	<0.1	0.3	25	0.17	
1456828	Rock	1.78	0.016	1.4	8.3	28.1	45	0.1	2.7	5.1	532	1.84	11.5	13.2	13.2	111	0.2	<0.1	0.3	14	1.89
REP 1456828	QC		1.3	9.0	25.3	45	0.1	2.5	4.9	521	1.84	10.1	10.3	13.1	124	0.3	<0.1	0.3	14	1.81	
1456843	Rock	1.94	0.006	0.6	7.6	9.8	58	<0.1	3.4	6.9	522	2.34	1.7	0.7	17.9	45	<0.1	<0.1	0.1	24	0.85
REP 1456843	QC		<0.005																		
1456857	Rock	1.78	0.028	2.5	18.9	101.9	70	0.4	7.0	6.8	848	2.06	17.9	16.3	16.5	75	0.7	0.1	1.9	21	1.89
REP 1456857	QC		0.024																		
Core Reject Duplicates																					
1456725	Rock	2.23	<0.005	1.0	7.1	6.9	66	<0.1	4.1	8.4	626	2.74	1.4	<0.5	21.7	43	<0.1	<0.1	<0.1	27	0.97
DUP 1456725	QC		<0.005	1.2	6.8	6.6	61	<0.1	4.1	8.1	614	2.67	1.4	<0.5	18.9	40	<0.1	<0.1	<0.1	27	0.92
1456759	Rock	1.81	0.245	9.3	33.1	36.4	65	0.8	7.6	7.8	362	3.36	43.4	293.8	21.7	30	0.7	0.2	1.2	19	0.13
DUP 1456759	QC		0.245	10.0	34.8	37.3	64	0.8	7.4	8.1	364	3.39	43.9	227.6	21.3	31	0.7	0.3	1.1	19	0.14
1456793	Rock	1.27	0.016	1.5	16.8	23.7	65	0.1	5.4	7.1	369	2.47	3.8	9.5	20.6	16	0.1	<0.1	0.3	23	0.17
DUP 1456793	QC		0.015	1.6	14.0	24.7	65	0.1	5.9	7.5	386	2.61	4.2	11.1	22.1	17	0.2	<0.1	0.4	24	0.17
1456827	Rock	2.21	0.017	1.5	8.0	8.9	56	<0.1	3.2	5.8	546	2.05	12.7	8.7	14.9	72	0.1	<0.1	<0.1	15	1.46
DUP 1456827	QC		0.011	1.4	7.3	8.5	54	<0.1	3.3	6.1	548	2.04	11.4	15.2	16.4	71	<0.1	<0.1	0.1	15	1.48
Reference Materials																					
STD DS10	Standard		13.8	155.7	151.5	366	2.0	75.5	12.9	856	2.72	45.2	62.0	7.3	63	2.8	8.6	12.0	43	1.02	
STD DS10	Standard		13.5	159.8	154.0	371	1.7	79.1	13.4	893	2.83	49.1	89.2	7.6	71	2.8	8.1	13.2	45	1.09	
STD DS10	Standard		15.0	160.3	156.1	364	1.8	77.3	13.3	888	2.75	44.8	99.6	8.0	71	2.6	8.6	12.8	43	1.07	
STD DS10	Standard		13.7	161.3	151.4	379	1.8	76.1	13.2	910	2.83	49.4	67.5	8.1	76	2.6	9.2	13.8	44	1.11	
STD DS10	Standard		15.1	163.3	151.0	366	1.9	76.8	13.5	906	2.80	46.5	63.5	7.8	67	3.0	9.8	12.7	43	1.09	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 1 of 3

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000421.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
REP 1456725	QC	0.046	52	9	0.64	175	0.102	<20	1.05	0.033	0.64	0.3	<0.01	4.2	0.2	<0.05	6	<0.5	<0.2
REP 1456759	QC	0.046	45	7	0.10	139	0.014	<20	0.55	0.006	0.21	0.3	0.09	4.6	<0.1	<0.05	2	<0.5	1.3
1456768	Rock	0.057	47	5	0.29	111	0.002	<20	0.28	0.008	0.22	0.7	0.08	3.1	<0.1	1.12	<1	0.7	3.6
REP 1456768	QC																		
1456770	Rock Pulp	0.059	5	31	0.74	97	0.124	<20	1.50	0.086	0.14	10.5	0.04	4.7	<0.1	<0.05	5	<0.5	<0.2
REP 1456770	QC																		
REP 1456793	QC	0.044	44	10	0.34	158	0.060	<20	1.15	0.024	0.52	0.5	0.02	6.3	0.2	<0.05	5	<0.5	<0.2
1456828	Rock	0.045	25	8	0.36	81	0.015	<20	0.44	0.018	0.25	1.0	<0.01	4.3	<0.1	0.19	2	<0.5	<0.2
REP 1456828	QC	0.044	25	8	0.36	85	0.015	<20	0.44	0.018	0.26	0.9	<0.01	4.3	<0.1	0.19	2	<0.5	<0.2
1456843	Rock	0.047	46	7	0.54	112	0.080	<20	0.94	0.023	0.47	0.4	<0.01	2.6	0.2	<0.05	5	<0.5	<0.2
REP 1456843	QC																		
1456857	Rock	0.050	41	8	0.22	383	0.006	<20	0.65	0.015	0.26	0.5	<0.01	4.0	<0.1	<0.05	3	<0.5	<0.2
REP 1456857	QC																		
Core Reject Duplicates																			
1456725	Rock	0.052	55	10	0.66	185	0.107	<20	1.08	0.034	0.66	0.3	<0.01	4.7	0.2	<0.05	7	<0.5	<0.2
DUP 1456725	QC	0.048	50	9	0.64	177	0.106	<20	1.04	0.033	0.64	0.3	<0.01	4.3	0.2	<0.05	6	<0.5	<0.2
1456759	Rock	0.046	43	6	0.10	135	0.014	<20	0.56	0.006	0.21	0.3	0.09	4.5	<0.1	<0.05	2	<0.5	1.3
DUP 1456759	QC	0.047	43	7	0.10	142	0.013	<20	0.55	0.006	0.22	0.3	0.10	4.3	<0.1	<0.05	2	<0.5	1.5
1456793	Rock	0.043	44	9	0.33	198	0.058	<20	1.07	0.019	0.48	0.5	0.01	6.3	0.2	<0.05	5	<0.5	<0.2
DUP 1456793	QC	0.046	45	10	0.34	158	0.060	<20	1.15	0.023	0.51	0.5	<0.01	6.5	0.1	<0.05	5	<0.5	<0.2
1456827	Rock	0.045	32	8	0.44	48	0.014	<20	0.43	0.020	0.23	0.9	<0.01	4.1	<0.1	0.08	2	<0.5	<0.2
DUP 1456827	QC	0.045	31	9	0.44	52	0.014	<20	0.43	0.018	0.23	0.9	<0.01	4.1	<0.1	0.08	2	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.075	17	54	0.77	393	0.075	<20	0.97	0.067	0.32	2.8	0.26	2.9	5.0	0.28	4	2.0	4.7
STD DS10	Standard	0.084	18	57	0.80	450	0.080	<20	1.04	0.073	0.34	2.8	0.28	3.1	5.4	0.29	5	2.0	5.1
STD DS10	Standard	0.076	19	57	0.80	419	0.087	<20	1.05	0.071	0.34	3.1	0.29	3.2	4.9	0.29	4	2.1	5.0
STD DS10	Standard	0.082	19	56	0.82	444	0.086	<20	1.07	0.072	0.35	3.1	0.29	3.2	5.2	0.29	5	2.3	5.1
STD DS10	Standard	0.086	19	56	0.79	402	0.083	<20	1.05	0.068	0.34	3.6	0.27	3.2	5.1	0.28	5	1.9	5.2



QUALITY CONTROL REPORT

WHI16000421.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OREAS45EA	Standard			1.7	732.7	15.7	32	0.3	409.1	56.2	431	23.16	11.5	49.7	11.2	4	<0.1	0.3	0.3	315	0.03
STD OREAS45EA	Standard			1.7	718.0	15.2	32	0.3	398.2	53.3	421	21.71	11.2	70.3	10.4	4	<0.1	0.3	0.3	307	0.03
STD OREAS45EA	Standard			1.6	722.4	15.8	32	0.3	399.6	55.2	414	22.97	11.7	52.0	11.4	4	<0.1	0.4	0.3	313	0.04
STD OREAS45EA	Standard			1.6	709.5	15.3	34	0.3	398.5	52.2	411	23.09	12.1	58.5	11.0	4	<0.1	0.3	0.3	315	0.04
STD OREAS45EA	Standard			1.8	732.2	16.2	32	0.3	412.0	55.9	450	22.21	11.7	67.8	11.6	4	<0.1	0.5	0.3	330	0.03
STD OXD108	Standard		0.412																		
STD OXD108	Standard		0.410																		
STD OXD108	Standard		0.423																		
STD OXI121	Standard		1.841																		
STD OXI121	Standard		1.843																		
STD OXI121	Standard		1.823																		
STD OXN117	Standard		7.753																		
STD OXN117	Standard		7.647																		
STD OXN117	Standard		7.448																		
STD OXD108 Expected			0.414																		
STD OXN117 Expected			7.679																		
STD OXI121 Expected			1.834																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01



QUALITY CONTROL REPORT

WHI16000421.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD OREAS45EA	Standard	0.029	7	896	0.10	148	0.104	<20	3.38	0.027	0.06	<0.1	0.01	79.4	<0.1	<0.05	13	0.8	<0.2
STD OREAS45EA	Standard	0.031	7	844	0.09	154	0.103	<20	3.22	0.022	0.06	<0.1	0.01	82.6	<0.1	<0.05	13	0.7	<0.2
STD OREAS45EA	Standard	0.031	8	843	0.10	148	0.110	<20	3.40	0.016	0.06	<0.1	<0.01	88.8	<0.1	<0.05	13	0.8	<0.2
STD OREAS45EA	Standard	0.032	8	829	0.11	155	0.108	<20	3.30	0.016	0.06	<0.1	<0.01	88.9	<0.1	<0.05	14	1.0	<0.2
STD OREAS45EA	Standard	0.032	8	888	0.11	154	0.102	<20	3.32	0.021	0.05	<0.1	0.01	86.9	<0.1	<0.05	14	1.2	<0.2
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXD108 Expected																			
STD OXN117 Expected																			
STD OXI121 Expected																			
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 3 of 3

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000421.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
Prep Wash																						
ROCK-WHI	Prep Blank		<0.005	0.8	4.0	1.4	31	<0.1	0.6	3.8	430	1.73	0.8	1.9	2.5	22	<0.1	<0.1	<0.1	23	0.56	
ROCK-WHI	Prep Blank		<0.005	0.5	2.8	1.4	31	<0.1	0.6	3.6	403	1.67	0.9	<0.5	2.6	25	<0.1	<0.1	<0.1	21	0.50	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 22, 2016

Page: 3 of 3 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000421.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.043	5	2	0.42	64	0.070	<20	0.86	0.076	0.08	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.042	5	2	0.39	67	0.069	<20	0.79	0.061	0.07	0.1	<0.01	2.2	<0.1	<0.05	3	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 02, 2016
Report Date: November 15, 2016
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI16000423.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV-10-30-2016 RAB
P.O. Number
Number of Samples: 73

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	68	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	73	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	73	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	73	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	73	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 2 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456934	Rock	2.95	0.093	13.7	73.2	13.1	55	0.8	5.3	7.5	497	3.32	22.7	87.7	3.0	65	0.2	9.6	0.6	17	0.10
1456935	Rock	3.09	0.028	1.5	355.4	18.6	97	1.1	9.2	17.5	1389	6.09	37.3	40.7	1.0	76	0.5	23.1	0.6	35	0.10
1456936	Rock	3.15	0.023	1.0	95.1	10.1	58	0.6	3.6	6.5	556	3.33	20.6	20.5	0.8	93	0.3	9.3	0.3	11	0.07
1456937	Rock	3.88	0.020	2.6	58.8	6.6	34	0.5	4.0	2.9	123	2.64	4.1	18.4	3.0	29	<0.1	0.8	0.2	11	0.06
1456938	Rock	2.96	0.025	0.9	79.6	11.4	38	0.7	2.6	2.5	132	3.14	6.6	21.0	2.4	45	<0.1	1.1	0.7	9	0.06
1456939	Rock	2.84	0.029	0.5	64.3	8.9	55	0.7	3.1	7.9	1448	3.44	6.6	28.4	2.5	38	0.3	1.8	0.2	14	0.40
1456940	Rock Pulp	0.12	2.429	63.4	2186.6	1244.3	3603	26.9	179.5	20.0	612	5.26	1166.2	1796.2	2.6	86	21.5	17.6	11.4	54	1.45
1456941	Rock	3.03	0.021	0.5	122.3	11.5	52	0.5	3.3	3.7	273	3.64	5.0	19.9	3.6	45	0.1	0.8	0.6	12	0.06
1456942	Rock	3.40	0.023	1.4	98.1	8.2	55	0.5	2.6	6.1	405	3.21	4.8	21.1	2.5	41	0.1	0.8	0.5	19	0.07
1456943	Rock	2.36	0.051	0.8	234.5	19.1	112	0.9	12.7	32.2	2345	5.98	14.5	49.8	0.9	101	1.6	6.0	0.8	80	1.82
1456944	Rock	3.13	0.011	0.6	33.1	12.2	49	0.2	5.9	8.0	714	2.18	0.9	9.8	1.4	60	0.2	0.4	0.1	40	1.69
1456945	Rock	1.95	0.008	0.5	22.1	24.8	15	0.2	1.4	2.5	234	0.89	0.9	7.6	1.2	34	<0.1	0.2	0.2	11	0.67
1456946	Rock	2.13	<0.005	0.6	6.2	25.5	9	0.2	1.0	1.1	147	0.53	0.8	3.8	0.6	56	0.2	0.1	0.2	4	0.61
1456947	Rock	3.08	0.008	0.6	24.0	180.8	29	0.8	2.0	4.3	349	1.29	1.0	5.5	0.9	78	0.3	0.2	1.5	20	1.72
1456948	Rock	2.14	0.015	0.9	70.1	146.9	47	0.9	4.3	7.3	513	2.00	1.3	17.4	1.5	59	0.3	0.2	1.3	30	1.91
1456949	Rock	2.25	0.030	1.0	61.9	500.0	53	2.7	3.6	8.5	493	2.57	1.8	28.0	1.8	57	0.5	0.3	5.0	37	1.46
1456950	Rock Pulp	0.12	<0.005	2.3	24.1	2.4	43	0.2	22.1	9.7	392	2.36	4.9	0.7	0.9	41	0.3	0.3	<0.1	57	0.77
1456951	Rock	1.61	0.009	8.0	27.8	63.7	28	0.4	1.9	3.1	406	0.95	<0.5	9.1	0.5	48	0.6	0.3	0.4	5	1.09
1456952	Rock	1.77	0.010	1.2	23.0	27.5	25	0.3	1.7	4.3	479	1.40	1.1	8.9	1.0	61	0.2	0.1	0.2	15	1.24
1456953	Rock	1.83	0.025	2.2	41.4	43.8	52	0.7	3.8	8.6	751	2.33	3.1	23.7	1.9	32	0.2	0.2	0.4	18	0.83
1456954	Rock	1.80	0.008	2.8	12.1	129.6	24	0.7	1.1	2.0	279	0.81	0.8	8.1	0.8	75	0.6	0.1	1.2	8	0.72
1456955	Rock	2.17	0.011	0.9	11.2	108.7	14	0.5	1.0	0.9	185	0.55	<0.5	5.8	0.4	49	0.6	<0.1	1.0	2	0.43
1456956	Rock	1.77	0.006	0.9	5.7	122.9	14	0.6	0.8	0.8	139	0.60	0.6	6.0	0.4	65	0.3	<0.1	1.1	3	0.46
1456957	Rock	2.23	<0.005	0.8	12.9	288.4	11	1.2	0.9	1.0	121	0.60	<0.5	2.9	0.5	70	0.4	<0.1	2.7	3	0.57
1456958	Rock	2.13	<0.005	1.1	3.3	28.1	9	0.1	1.0	0.9	162	0.50	<0.5	4.8	0.4	53	<0.1	<0.1	0.2	3	0.74
1456959	Rock	2.20	<0.005	0.8	3.4	10.2	7	<0.1	1.0	0.5	184	0.49	<0.5	0.9	0.7	41	<0.1	<0.1	<0.1	3	0.80
1456960	Rock	2.11	<0.005	0.8	2.9	9.7	7	<0.1	1.1	0.5	183	0.53	0.6	1.3	0.7	43	<0.1	<0.1	<0.1	3	0.78
1456961	Rock	2.20	0.008	0.8	4.4	28.2	10	0.2	1.6	1.0	179	0.65	0.5	6.7	0.6	59	0.3	<0.1	0.2	4	0.70
1456962	Rock	2.40	0.007	1.2	16.6	13.4	11	0.3	1.5	1.3	206	0.76	0.7	3.4	0.7	57	0.2	0.1	0.2	4	0.56
1456963	Rock	3.04	0.009	4.3	33.9	26.1	51	0.4	3.5	8.4	552	2.42	1.1	8.6	2.0	97	<0.1	0.2	0.3	22	1.57



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm		
1456934	Rock	0.047	14	4	0.04	255	0.001	<20	0.30	0.013	0.36	0.3	0.12	7.8	<0.1	0.40	2	0.8	1.0	
1456935	Rock	0.097	7	5	0.05	219	0.002	<20	0.37	0.010	0.33	0.3	0.22	17.5	<0.1	0.34	2	1.4	1.3	
1456936	Rock	0.072	6	4	0.02	106	0.001	<20	0.26	0.012	0.38	0.7	0.13	13.0	<0.1	0.47	1	1.5	1.0	
1456937	Rock	0.039	8	5	0.03	100	<0.001	<20	0.24	0.014	0.19	1.3	0.10	5.4	<0.1	0.11	1	1.0	0.7	
1456938	Rock	0.050	12	4	0.03	162	0.001	<20	0.29	0.017	0.30	0.8	0.10	7.3	<0.1	0.29	1	1.8	0.7	
1456939	Rock	0.056	14	3	0.09	67	<0.001	<20	0.25	0.015	0.24	1.0	0.09	10.3	<0.1	0.77	1	1.6	1.0	
1456940	Rock Pulp	0.064	12	43	0.84	265	0.083	<20	1.47	0.081	0.19	8.9	0.71	4.4	1.4	1.51	6	3.5	0.7	
1456941	Rock	0.055	14	5	0.04	104	0.001	<20	0.30	0.024	0.34	0.5	0.11	10.9	<0.1	0.38	1	0.9	0.6	
1456942	Rock	0.047	13	3	0.03	83	0.002	<20	0.26	0.018	0.20	0.7	0.11	9.4	<0.1	0.11	1	1.4	0.6	
1456943	Rock	0.084	8	13	0.53	694	0.013	<20	0.65	0.022	0.32	0.4	0.18	23.8	<0.1	0.18	3	0.7	1.2	
1456944	Rock	0.030	8	10	0.30	534	0.012	<20	0.30	0.031	0.15	0.6	<0.01	9.6	<0.1	0.06	2	<0.5	<0.2	
1456945	Rock	0.014	5	4	0.06	452	0.003	<20	0.23	0.041	0.16	0.4	<0.01	3.1	<0.1	<0.05	<1	<0.5	<0.2	
1456946	Rock	0.007	2	4	0.08	896	<0.001	<20	0.16	0.040	0.13	0.8	<0.01	1.0	<0.1	0.08	<1	<0.5	<0.2	
1456947	Rock	0.020	5	5	0.06	731	0.005	<20	0.20	0.041	0.15	1.1	<0.01	4.5	<0.1	0.15	<1	<0.5	<0.2	
1456948	Rock	0.034	8	6	0.11	355	0.007	<20	0.24	0.030	0.17	1.1	0.02	7.7	<0.1	0.26	1	<0.5	0.2	
1456949	Rock	0.043	9	6	0.10	591	0.010	<20	0.30	0.026	0.21	1.0	0.02	9.3	<0.1	0.48	2	1.9	0.6	
1456950	Rock Pulp	0.061	4	29	0.76	96	0.116	<20	1.51	0.078	0.13	13.2	<0.01	4.8	<0.1	<0.05	5	<0.5	<0.2	
1456951	Rock	0.007	2	4	0.09	445	<0.001	<20	0.15	0.027	0.11	1.3	0.02	2.2	<0.1	0.12	<1	<0.5	<0.2	
1456952	Rock	0.021	5	5	0.09	499	0.003	<20	0.21	0.036	0.15	1.1	0.01	4.8	<0.1	0.16	<1	<0.5	0.2	
1456953	Rock	0.029	6	4	0.08	276	0.002	<20	0.25	0.019	0.18	0.7	0.07	6.8	<0.1	0.13	<1	<0.5	0.5	
1456954	Rock	0.009	3	4	0.05	765	<0.001	<20	0.17	0.039	0.14	1.6	<0.01	2.1	<0.1	0.16	<1	<0.5	<0.2	
1456955	Rock	0.005	1	4	0.02	588	<0.001	<20	0.14	0.023	0.13	1.1	<0.01	1.0	<0.1	0.13	<1	<0.5	<0.2	
1456956	Rock	0.005	1	4	0.02	861	<0.001	<20	0.17	0.037	0.16	1.4	<0.01	1.0	<0.1	0.15	<1	<0.5	<0.2	
1456957	Rock	0.007	1	5	0.02	1087	<0.001	<20	0.15	0.057	0.12	2.1	<0.01	0.9	<0.1	0.18	<1	<0.5	<0.2	
1456958	Rock	0.006	1	7	0.04	690	<0.001	<20	0.17	0.048	0.15	1.9	<0.01	1.0	<0.1	0.08	<1	<0.5	<0.2	
1456959	Rock	0.007	2	5	0.05	534	<0.001	<20	0.17	0.038	0.15	1.0	<0.01	1.1	<0.1	<0.05	<1	<0.5	<0.2	
1456960	Rock	0.007	2	5	0.05	551	<0.001	<20	0.20	0.046	0.16	0.9	<0.01	1.0	<0.1	<0.05	<1	<0.5	<0.2	
1456961	Rock	0.008	2	5	0.03	715	<0.001	<20	0.14	0.039	0.12	1.5	<0.01	1.1	<0.1	0.16	<1	<0.5	<0.2	
1456962	Rock	0.008	2	6	0.07	805	<0.001	<20	0.15	0.034	0.13	1.6	<0.01	1.4	<0.1	0.17	<1	<0.5	0.3	
1456963	Rock	0.043	9	6	0.37	54	0.004	<20	0.22	0.029	0.16	0.8	<0.01	8.9	<0.1	0.54	<1	1.1	0.3	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 3 of 4 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456964	Rock	3.14	<0.005	0.8	41.6	15.6	48	0.2	3.7	7.9	536	2.45	0.8	2.4	2.1	144	0.2	0.1	0.2	26	1.74
1456965	Rock	2.96	0.025	1.4	83.3	11.8	81	0.9	4.4	8.5	559	2.75	3.4	22.4	2.0	150	0.4	0.2	0.2	28	1.19
1456966	Rock	2.43	0.022	1.5	28.7	23.8	33	0.4	4.6	6.5	482	1.94	1.9	23.8	2.0	85	<0.1	0.2	0.3	21	1.15
1456967	Rock	2.88	0.020	1.4	27.8	12.7	28	0.3	4.0	3.8	399	1.49	1.2	17.3	2.0	86	0.2	<0.1	0.1	14	0.98
1456968	Rock	2.18	<0.005	1.0	10.9	11.6	17	<0.1	1.7	1.6	347	0.90	0.7	3.3	0.9	79	0.2	<0.1	<0.1	7	0.82
1456969	Rock	2.53	0.005	1.6	77.3	20.6	52	0.2	2.1	5.2	504	1.96	1.0	5.1	2.8	42	0.2	0.2	0.2	30	0.95
1456970	Rock Pulp	0.15	0.842	4.2	31.5	5.2	50	0.2	22.0	8.7	391	2.46	6.4	417.7	0.9	44	0.2	0.9	0.1	60	0.82
1456971	Rock	2.82	0.014	3.0	33.6	60.1	56	0.4	2.2	4.5	393	1.81	0.6	12.7	3.1	29	0.4	0.3	0.5	22	0.69
1456972	Rock	3.13	0.013	3.6	36.3	87.1	34	0.6	3.4	5.2	501	1.82	1.0	13.9	3.3	30	0.1	0.2	0.8	29	1.48
1456973	Rock	2.18	0.008	1.0	17.4	29.5	29	0.3	2.8	4.5	542	1.46	0.7	8.6	9.8	38	0.2	0.2	0.3	27	1.39
1456974	Rock	2.43	0.011	1.3	32.3	41.4	76	0.4	17.3	13.3	963	2.98	0.9	12.5	2.1	99	0.3	0.3	0.5	98	3.15
1456975	Rock	3.63	<0.005	0.7	58.3	100.0	75	0.2	37.5	24.9	1318	4.30	1.1	1.1	0.5	170	0.3	0.5	1.0	160	5.25
1456976	Rock	2.95	<0.005	0.4	23.7	31.1	84	0.2	49.4	30.2	1540	4.78	1.4	2.1	0.4	147	0.2	0.8	0.3	187	5.74
1456977	Rock	3.44	0.007	0.5	25.2	121.6	91	0.4	48.4	29.0	1541	4.74	1.1	5.0	0.4	166	0.4	0.5	1.2	200	5.25
1456978	Rock	2.89	0.092	15.5	101.1	276.2	153	2.8	30.3	20.6	1133	3.63	2.4	93.7	0.6	103	1.4	0.6	2.8	115	2.73
1456979	Rock	2.83	0.092	33.6	162.6	64.3	49	3.2	10.9	9.0	1138	2.39	2.7	90.9	1.2	59	0.7	0.8	0.9	12	2.13
1456980	Rock Pulp	0.13	<0.005	2.3	23.7	2.4	43	0.2	22.3	9.9	399	2.40	4.2	<0.5	1.0	43	0.2	0.3	<0.1	61	0.84
1456981	Rock	2.73	0.074	116.9	160.5	127.1	61	4.1	19.0	13.6	1394	3.06	3.6	72.4	1.3	75	0.9	1.2	1.5	31	2.58
1456982	Rock	2.80	0.025	7.1	54.1	58.4	54	1.2	8.1	7.8	771	2.18	2.0	25.3	1.4	66	0.6	0.4	0.7	31	1.54
1456983	Rock	3.68	0.081	5.4	26.3	135.3	64	2.1	2.3	4.7	433	1.94	0.9	76.3	2.1	57	1.1	0.2	1.6	24	0.85
1456984	Rock	4.42	0.046	11.1	72.5	67.9	53	1.4	6.8	6.0	883	1.82	1.6	46.8	1.1	52	0.4	0.4	0.7	22	2.05
1456985	Rock	3.36	0.058	42.0	165.2	88.5	54	3.1	7.0	6.2	985	1.75	1.8	56.1	0.9	70	1.0	0.5	0.8	8	2.05
1456986	Rock	3.32	0.064	63.9	405.7	216.4	110	4.8	12.1	9.4	1630	2.32	2.0	65.3	0.7	83	2.8	0.5	1.7	12	3.04
1456987	Rock	3.80	0.029	10.2	142.7	87.0	73	1.4	4.9	5.9	666	1.89	1.7	25.9	1.9	47	1.0	0.3	0.9	18	1.49
1456988	Rock	3.46	0.032	7.0	30.1	125.1	93	0.9	7.8	10.8	761	2.39	1.1	31.3	1.4	78	1.3	0.3	1.3	72	2.37
1456989	Rock	4.06	0.132	1.1	49.0	21.9	85	2.6	18.5	21.0	1542	4.09	2.7	127.4	0.5	120	0.3	0.4	0.2	115	5.28
1456990	Rock	2.52	0.099	5.6	28.6	44.7	36	2.5	5.7	10.0	611	2.08	10.4	104.6	5.4	50	0.3	0.4	0.6	17	2.28
1456991	Rock	2.44	0.132	7.4	45.0	80.0	42	3.6	9.5	14.4	787	2.47	13.4	135.5	4.2	57	0.3	0.7	1.1	25	2.54
1456992	Rock	2.79	0.088	4.1	11.0	11.0	31	1.7	28.9	7.6	512	2.39	6.2	91.9	6.0	37	0.3	0.3	0.3	9	2.51
1456993	Rock	2.80	0.123	2.0	15.6	8.1	16	1.5	2.2	4.8	231	1.64	5.1	127.4	8.1	36	<0.1	0.2	0.1	6	1.35



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456964	Rock	0.041	10	6	0.47	86	0.005	<20	0.26	0.027	0.18	0.5	0.01	8.8	<0.1	0.17	<1	<0.5	<0.2
1456965	Rock	0.045	9	9	0.44	253	0.008	<20	0.29	0.032	0.17	1.7	0.02	9.3	<0.1	1.08	2	1.3	0.8
1456966	Rock	0.027	8	10	0.41	312	0.005	<20	0.24	0.031	0.15	2.1	0.02	7.1	<0.1	0.70	1	<0.5	0.3
1456967	Rock	0.020	9	6	0.34	230	0.004	<20	0.17	0.040	0.12	2.3	0.01	4.6	<0.1	0.45	<1	<0.5	<0.2
1456968	Rock	0.011	4	6	0.26	1212	0.002	<20	0.16	0.049	0.12	1.7	<0.01	2.0	<0.1	0.17	<1	<0.5	<0.2
1456969	Rock	0.028	11	7	0.45	522	0.009	<20	0.29	0.049	0.10	2.5	<0.01	6.5	<0.1	0.39	2	<0.5	<0.2
1456970	Rock Pulp	0.053	5	30	0.72	94	0.126	<20	1.51	0.086	0.13	9.9	0.05	5.1	<0.1	<0.05	5	<0.5	<0.2
1456971	Rock	0.032	12	7	0.39	421	0.014	<20	0.35	0.065	0.12	1.5	<0.01	5.8	<0.1	0.29	2	<0.5	<0.2
1456972	Rock	0.034	11	9	0.53	73	0.008	<20	0.25	0.043	0.15	1.4	<0.01	6.5	<0.1	0.35	1	<0.5	0.2
1456973	Rock	0.019	16	7	0.53	493	0.008	<20	0.25	0.053	0.13	1.6	<0.01	3.7	<0.1	0.32	1	0.6	<0.2
1456974	Rock	0.060	9	47	1.30	600	0.024	<20	0.88	0.041	0.22	1.3	<0.01	12.2	<0.1	0.43	5	<0.5	<0.2
1456975	Rock	0.029	4	111	2.51	172	0.059	<20	1.59	0.052	0.44	0.3	<0.01	21.4	0.1	0.18	7	0.9	<0.2
1456976	Rock	0.033	4	145	2.88	196	0.059	<20	2.01	0.034	0.46	0.2	<0.01	26.4	0.1	0.22	8	<0.5	<0.2
1456977	Rock	0.033	4	144	2.89	204	0.040	<20	2.17	0.039	0.36	0.3	<0.01	27.4	0.1	0.19	9	<0.5	<0.2
1456978	Rock	0.021	5	78	1.78	352	0.012	<20	1.35	0.019	0.16	2.7	0.02	15.6	<0.1	1.16	7	1.8	1.1
1456979	Rock	0.012	7	13	0.61	214	0.001	<20	0.22	0.005	0.16	4.2	0.03	9.7	<0.1	2.13	1	<0.5	2.1
1456980	Rock Pulp	0.060	4	30	0.77	95	0.128	<20	1.56	0.082	0.14	12.2	<0.01	5.1	<0.1	<0.05	5	<0.5	<0.2
1456981	Rock	0.012	7	28	0.84	202	0.004	<20	0.46	0.008	0.22	3.1	0.04	13.9	0.1	2.66	3	2.2	2.2
1456982	Rock	0.019	6	19	0.55	260	0.007	<20	0.45	0.021	0.15	3.0	<0.01	8.2	<0.1	1.31	3	0.9	0.7
1456983	Rock	0.021	9	10	0.42	374	0.006	<20	0.37	0.035	0.14	3.1	<0.01	5.9	<0.1	1.08	3	<0.5	1.3
1456984	Rock	0.013	6	16	0.68	498	0.002	<20	0.36	0.009	0.16	3.1	0.02	6.0	<0.1	0.81	3	<0.5	0.9
1456985	Rock	0.008	7	11	0.46	369	<0.001	<20	0.15	0.005	0.14	5.9	0.03	7.6	<0.1	1.40	<1	1.0	1.9
1456986	Rock	0.007	6	13	0.75	297	<0.001	<20	0.19	0.004	0.14	3.8	0.05	11.8	<0.1	1.88	1	1.6	2.1
1456987	Rock	0.022	10	10	0.49	227	0.004	<20	0.33	0.023	0.17	1.6	0.03	6.8	<0.1	0.70	2	<0.5	0.8
1456988	Rock	0.025	7	11	0.77	528	0.011	<20	0.47	0.026	0.23	1.1	0.02	9.9	<0.1	0.73	3	<0.5	0.4
1456989	Rock	0.019	4	24	1.20	203	0.023	<20	0.97	0.025	0.63	0.6	0.04	26.6	0.2	1.22	4	0.9	1.7
1456990	Rock	0.027	17	9	0.18	142	0.001	<20	0.27	0.006	0.22	1.7	0.03	7.4	<0.1	1.45	1	0.8	2.0
1456991	Rock	0.028	13	9	0.27	142	0.001	<20	0.37	0.008	0.28	1.1	0.03	10.6	<0.1	1.38	1	1.0	2.5
1456992	Rock	0.042	18	17	0.07	80	<0.001	<20	0.24	0.003	0.20	2.3	0.02	5.1	<0.1	2.41	<1	1.3	1.9
1456993	Rock	0.032	22	9	0.04	227	<0.001	<20	0.25	0.004	0.24	2.6	0.01	2.3	<0.1	1.58	1	<0.5	1.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 4 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456994	Rock	2.90	0.040	1.7	6.3	6.1	24	0.6	1.2	1.5	297	0.78	3.3	39.5	0.8	51	<0.1	0.1	<0.1	3	1.72
1456995	Rock	2.41	0.118	2.0	11.8	8.5	22	1.4	3.1	5.8	410	1.84	9.9	109.1	8.2	45	<0.1	0.2	0.2	7	1.77
1456996	Rock	2.72	0.174	1.5	15.4	9.5	27	1.7	2.7	5.3	416	2.09	12.1	172.9	8.3	45	0.1	0.3	0.2	7	1.82
1456997	Rock	2.64	0.118	1.8	14.2	10.3	44	1.8	2.8	4.9	527	2.05	9.6	113.8	6.0	55	0.1	0.2	0.3	9	2.76
1456998	Rock	3.03	0.104	3.5	17.5	11.1	30	1.5	3.6	5.1	490	1.93	7.3	100.9	4.7	50	<0.1	0.3	0.2	9	2.58
1456999	Rock	3.11	0.042	4.0	11.4	10.0	25	0.9	3.9	4.5	393	1.93	8.3	44.1	4.9	54	0.1	0.2	0.2	7	1.83
1457000	Rock Pulp	0.12	2.470	61.5	2058.2	1221.4	3370	25.4	173.1	18.5	575	4.82	1097.8	1325.1	2.5	81	18.9	18.3	9.7	54	1.43
1464001	Rock	2.20	0.029	2.1	11.9	6.4	11	0.4	1.6	4.0	234	1.22	5.3	28.8	4.7	38	<0.1	0.2	0.1	5	1.23
1464002	Rock	2.08	0.038	1.6	10.7	7.3	20	0.5	2.3	3.3	406	1.33	4.5	33.6	2.4	54	0.1	0.2	0.1	5	1.91
1464003	Rock	2.99	0.038	1.9	6.0	7.1	14	0.4	1.5	2.6	293	0.89	3.2	37.8	0.5	45	<0.1	0.1	0.1	4	1.38
1464004	Rock	3.57	0.076	4.0	18.4	9.2	21	0.6	2.0	4.7	496	1.52	5.1	69.2	4.9	44	0.1	0.1	<0.1	7	2.29
1464005	Rock	3.95	0.068	2.6	14.4	10.8	41	0.6	3.6	7.0	573	2.34	5.7	56.8	5.6	56	<0.1	0.2	0.2	21	2.42
1464006	Rock	2.82	0.038	2.0	9.8	6.2	23	0.2	1.8	3.6	347	1.48	2.1	30.4	3.3	40	<0.1	<0.1	<0.1	11	1.52



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000423.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1456994	Rock	0.010	4	8	0.06	475	<0.001	<20	0.17	0.005	0.22	2.4	<0.01	1.3	<0.1	0.58	<1	<0.5	0.5
1456995	Rock	0.039	23	8	0.15	173	<0.001	<20	0.27	0.007	0.26	2.6	<0.01	3.2	<0.1	1.60	<1	1.0	1.5
1456996	Rock	0.045	25	7	0.16	184	<0.001	<20	0.27	0.007	0.26	1.9	0.02	3.1	<0.1	1.87	<1	1.1	1.7
1456997	Rock	0.050	21	7	0.15	219	<0.001	<20	0.29	0.004	0.25	1.9	0.02	4.2	<0.1	1.88	<1	1.1	1.6
1456998	Rock	0.043	15	7	0.16	275	<0.001	<20	0.24	0.003	0.20	2.3	0.02	3.5	<0.1	1.77	<1	1.0	1.8
1456999	Rock	0.036	14	8	0.14	210	<0.001	<20	0.25	0.006	0.25	2.5	0.02	2.8	<0.1	1.77	<1	1.7	1.1
1457000	Rock Pulp	0.060	11	42	0.80	277	0.086	<20	1.41	0.079	0.18	8.2	0.70	4.0	1.4	1.44	6	3.0	0.5
1464001	Rock	0.026	10	8	0.09	227	<0.001	<20	0.25	0.013	0.22	2.0	0.02	1.6	<0.1	1.02	<1	<0.5	0.6
1464002	Rock	0.022	5	8	0.23	422	<0.001	<20	0.29	0.009	0.26	1.9	0.02	1.7	<0.1	0.95	<1	<0.5	0.8
1464003	Rock	0.009	2	9	0.12	245	<0.001	<20	0.21	0.006	0.22	2.1	0.01	1.7	<0.1	0.53	<1	<0.5	1.0
1464004	Rock	0.028	12	9	0.17	83	<0.001	<20	0.30	0.013	0.27	1.1	0.02	2.5	<0.1	0.64	<1	<0.5	0.8
1464005	Rock	0.053	15	9	0.40	292	0.002	<20	0.46	0.021	0.34	0.7	0.05	5.1	<0.1	0.61	2	<0.5	1.1
1464006	Rock	0.047	7	8	0.19	175	<0.001	<20	0.40	0.034	0.33	0.6	0.05	2.3	<0.1	0.32	1	<0.5	0.3



QUALITY CONTROL REPORT

WHI16000423.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1456936	Rock	3.15	0.023	1.0	95.1	10.1	58	0.6	3.6	6.5	556	3.33	20.6	20.5	0.8	93	0.3	9.3	0.3	11	0.07
REP 1456936	QC			1.3	99.7	10.4	60	0.6	3.8	7.1	582	3.53	21.1	20.7	0.8	97	0.4	9.3	0.3	12	0.07
1456953	Rock	1.83	0.025	2.2	41.4	43.8	52	0.7	3.8	8.6	751	2.33	3.1	23.7	1.9	32	0.2	0.2	0.4	18	0.83
REP 1456953	QC		0.026																		
1456969	Rock	2.53	0.005	1.6	77.3	20.6	52	0.2	2.1	5.2	504	1.96	1.0	5.1	2.8	42	0.2	0.2	0.2	30	0.95
REP 1456969	QC			1.4	78.7	21.1	55	0.2	2.0	5.3	506	1.99	1.4	3.5	2.9	43	0.3	0.2	0.2	30	0.97
1456993	Rock	2.80	0.123	2.0	15.6	8.1	16	1.5	2.2	4.8	231	1.64	5.1	127.4	8.1	36	<0.1	0.2	0.1	6	1.35
REP 1456993	QC		0.116																		
1464002	Rock	2.08	0.038	1.6	10.7	7.3	20	0.5	2.3	3.3	406	1.33	4.5	33.6	2.4	54	0.1	0.2	0.1	5	1.91
REP 1464002	QC			1.9	9.9	7.1	18	0.5	1.9	3.4	413	1.34	4.9	36.6	2.4	53	0.1	0.2	0.1	5	1.92
Core Reject Duplicates																					
1456942	Rock	3.40	0.023	1.4	98.1	8.2	55	0.5	2.6	6.1	405	3.21	4.8	21.1	2.5	41	0.1	0.8	0.5	19	0.07
DUP 1456942	QC		0.022	1.4	91.3	8.0	51	0.5	2.9	6.2	387	3.16	4.6	20.6	2.5	41	0.1	0.8	0.5	19	0.07
1456976	Rock	2.95	<0.005	0.4	23.7	31.1	84	0.2	49.4	30.2	1540	4.78	1.4	2.1	0.4	147	0.2	0.8	0.3	187	5.74
DUP 1456976	QC		<0.005	0.4	21.4	33.3	86	0.2	51.2	30.4	1551	4.80	1.1	2.1	0.5	148	0.2	0.7	0.3	189	5.78
Reference Materials																					
STD DS10	Standard			13.0	151.1	148.1	353	1.8	72.1	12.2	860	2.74	43.6	89.9	7.7	73	2.4	9.0	13.0	44	1.05
STD DS10	Standard			14.2	143.0	149.5	338	1.9	70.2	12.3	828	2.70	42.7	136.2	7.5	70	2.1	8.8	12.3	42	1.04
STD DS10	Standard			14.3	151.6	153.6	364	1.9	72.4	12.7	853	2.76	43.4	85.7	7.7	71	2.9	8.4	13.3	42	1.06
STD OREAS45EA	Standard			1.6	677.0	13.7	30	0.2	378.8	49.6	397	20.74	11.6	49.2	10.1	4	<0.1	0.2	0.3	292	0.03
STD OREAS45EA	Standard			1.4	646.5	13.0	28	0.2	371.0	47.7	382	19.84	11.2	47.0	9.1	4	<0.1	0.3	0.2	280	0.03
STD OREAS45EA	Standard			1.7	657.1	13.8	30	0.2	365.3	48.6	391	20.24	11.5	52.3	9.6	4	<0.1	0.4	0.3	282	0.03
STD OXD108	Standard		0.412																		
STD OXI121	Standard		1.832																		
STD OXN117	Standard		7.904																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXD108 Expected			0.414																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000423.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1456936	Rock	0.072	6	4	0.02	106	0.001	<20	0.26	0.012	0.38	0.7	0.13	13.0	<0.1	0.47	1	1.5	1.0
REP 1456936	QC	0.074	6	7	0.02	111	0.001	<20	0.27	0.013	0.40	0.8	0.12	14.0	<0.1	0.49	1	<0.5	0.8
1456953	Rock	0.029	6	4	0.08	276	0.002	<20	0.25	0.019	0.18	0.7	0.07	6.8	<0.1	0.13	<1	<0.5	0.5
REP 1456953	QC																		
1456969	Rock	0.028	11	7	0.45	522	0.009	<20	0.29	0.049	0.10	2.5	<0.01	6.5	<0.1	0.39	2	<0.5	<0.2
REP 1456969	QC	0.031	10	8	0.46	526	0.010	<20	0.29	0.049	0.10	2.6	<0.01	6.1	<0.1	0.40	2	<0.5	<0.2
1456993	Rock	0.032	22	9	0.04	227	<0.001	<20	0.25	0.004	0.24	2.6	0.01	2.3	<0.1	1.58	1	<0.5	1.2
REP 1456993	QC																		
1464002	Rock	0.022	5	8	0.23	422	<0.001	<20	0.29	0.009	0.26	1.9	0.02	1.7	<0.1	0.95	<1	<0.5	0.8
REP 1464002	QC	0.023	5	8	0.24	414	<0.001	<20	0.29	0.010	0.26	1.9	0.01	1.7	<0.1	0.95	<1	<0.5	0.7
Core Reject Duplicates																			
1456942	Rock	0.047	13	3	0.03	83	0.002	<20	0.26	0.018	0.20	0.7	0.11	9.4	<0.1	0.11	1	1.4	0.6
DUP 1456942	QC	0.048	13	3	0.03	84	0.002	<20	0.26	0.019	0.20	0.6	0.12	9.6	<0.1	0.11	1	0.9	0.5
1456976	Rock	0.033	4	145	2.88	196	0.059	<20	2.01	0.034	0.46	0.2	<0.01	26.4	0.1	0.22	8	<0.5	<0.2
DUP 1456976	QC	0.034	4	147	2.91	194	0.058	<20	2.04	0.036	0.46	0.2	<0.01	26.8	0.1	0.22	8	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.072	19	53	0.77	421	0.080	<20	1.05	0.070	0.33	3.0	0.30	2.9	4.8	0.27	4	1.7	4.8
STD DS10	Standard	0.076	18	52	0.75	410	0.078	<20	1.01	0.070	0.33	2.9	0.27	2.9	5.2	0.28	4	2.1	4.8
STD DS10	Standard	0.075	18	54	0.77	414	0.075	<20	1.00	0.070	0.33	3.1	0.28	3.1	5.5	0.29	4	2.3	4.7
STD OREAS45EA	Standard	0.029	7	779	0.10	139	0.094	<20	3.17	0.019	0.05	<0.1	0.02	81.9	<0.1	<0.05	12	1.0	<0.2
STD OREAS45EA	Standard	0.027	7	750	0.09	133	0.091	<20	3.12	0.020	0.05	<0.1	<0.01	79.0	<0.1	<0.05	11	0.6	<0.2
STD OREAS45EA	Standard	0.029	7	758	0.09	137	0.093	<20	3.07	0.020	0.05	<0.1	0.01	78.8	<0.1	<0.05	12	1.9	<0.2
STD OXD108	Standard																		
STD OXI121	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXD108 Expected																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 2 of 2 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000423.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD OXN117 Expected		7.679																				
STD OXI121 Expected		1.834																				
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
Prep Wash																						
ROCK-WHI	Prep Blank	<0.005	0.7	4.6	2.1	30	<0.1	0.8	3.5	406	1.68	0.9	<0.5	2.3	26	<0.1	<0.1	<0.1	22	0.55		
ROCK-WHI	Prep Blank	<0.005	0.5	4.0	1.8	34	<0.1	0.7	3.7	437	1.76	0.9	<0.5	2.5	29	<0.1	<0.1	<0.1	23	0.61		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 15, 2016

Page: 2 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000423.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD OXN117	Expected																		
STD OXI121	Expected																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.040	5	2	0.39	65	0.082	<20	0.86	0.087	0.10	0.2	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.041	6	2	0.41	72	0.087	<20	0.91	0.100	0.10	0.1	<0.01	2.9	<0.1	<0.05	4	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 02, 2016
Report Date: November 25, 2016
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI16000429.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV-10-30-2016 RAB
P.O. Number
Number of Samples: 75

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	70	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	75	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	75	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	75	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	75	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. *** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 2 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456859	Rock	2.14	<0.005	1.8	16.7	14.9	63	<0.1	4.0	7.6	653	2.27	2.1	3.0	17.9	127	0.2	0.1	0.2	26	1.73
1456860	Rock	2.44	0.006	1.7	15.3	14.9	62	<0.1	3.8	7.6	632	2.38	2.0	2.9	18.5	125	0.2	0.1	0.2	27	1.66
1456861	Rock	2.70	<0.005	1.4	10.1	13.5	59	<0.1	9.9	8.0	535	2.30	1.7	2.0	14.9	98	0.3	0.1	0.2	35	1.62
1456862	Rock	2.44	<0.005	2.3	15.2	32.1	83	<0.1	12.3	8.6	911	2.45	3.8	2.0	15.6	165	0.6	0.2	0.5	41	2.80
1456863	Rock	2.28	<0.005	1.5	9.1	13.0	60	<0.1	4.2	7.9	549	2.51	2.0	1.1	19.6	89	0.2	0.1	0.2	25	1.58
1456864	Rock	2.62	0.010	2.0	17.5	13.5	62	<0.1	4.1	9.0	617	2.56	4.5	6.7	18.5	77	0.2	0.1	0.2	26	1.51
1456865	Rock	1.59	0.011	1.8	24.3	15.1	60	0.1	3.9	8.6	571	2.52	6.5	7.5	19.9	90	0.2	0.1	0.2	25	1.50
1456866	Rock	1.71	0.009	2.7	18.0	31.1	62	0.3	3.6	7.5	386	2.14	8.2	7.3	17.9	46	0.5	0.1	0.8	18	0.91
1456867	Rock	1.86	0.008	2.9	9.8	17.0	61	0.1	3.5	7.2	493	2.43	7.4	6.3	18.9	53	0.2	<0.1	0.3	16	0.78
1456868	Rock	2.03	<0.005	1.9	17.2	13.6	59	<0.1	3.1	7.1	611	2.41	4.4	1.8	18.2	87	0.2	0.1	0.2	19	1.84
1456869	Rock	2.38	<0.005	0.9	7.9	8.9	77	<0.1	2.3	6.2	612	2.71	3.1	0.9	7.0	109	0.2	<0.1	0.1	23	2.36
1456870	Rock Pulp	0.12	0.920	4.3	35.1	5.5	51	0.2	24.3	10.0	393	2.49	6.6	316.0	0.9	40	0.2	0.8	0.1	58	0.79
1456871	Rock	1.34	0.021	0.7	18.0	13.3	60	0.1	2.6	6.1	584	2.38	16.0	18.3	18.7	123	0.3	<0.1	0.3	9	2.31
1456872	Rock	2.38	0.058	2.4	17.3	20.8	55	0.5	3.8	9.1	441	2.43	54.9	58.1	18.2	64	0.2	0.2	0.3	6	1.53
1456873	Rock	2.00	0.824	11.8	26.8	44.7	180	1.6	11.4	15.3	823	3.75	103.2	881.3	15.5	31	1.8	0.5	0.8	12	0.28
1456874	Rock	1.57	0.485	2.5	19.6	29.9	61	1.1	6.4	11.5	720	2.74	47.8	385.9	18.0	58	0.3	0.3	0.6	14	1.69
1456875	Rock	3.04	0.169	1.3	9.2	19.5	59	0.5	3.6	6.5	872	2.22	49.4	186.6	13.3	92	0.3	0.2	0.4	13	2.41
1456876	Rock	2.61	0.855	1.1	21.4	63.3	79	1.3	19.6	8.5	958	2.71	53.1	2840.7	16.9	89	1.0	0.2	0.9	29	2.72
1456877	Rock	2.84	1.065	5.3	30.2	38.5	77	2.5	43.3	16.3	925	3.63	229.0	1369.3	13.7	71	0.6	0.8	1.1	19	2.42
1456878	Rock	2.36	0.573	26.3	19.7	30.5	52	1.1	7.4	14.3	2294	3.32	143.4	596.8	17.9	86	0.6	0.6	1.0	11	1.66
1456879	Rock	2.10	0.007	1.8	10.6	6.9	46	<0.1	3.4	6.6	455	2.12	3.0	3.2	17.6	14	<0.1	0.1	0.2	20	0.21
1456880	Rock Pulp	0.12	<0.005	2.3	24.7	2.4	43	0.2	23.8	10.8	412	2.45	4.6	1.7	1.0	43	0.1	0.3	<0.1	59	0.86
1456881	Rock	2.62	<0.005	2.1	8.2	8.2	58	<0.1	4.5	6.0	627	2.33	4.2	1.1	14.7	15	<0.1	<0.1	0.1	21	0.24
1456882	Rock	2.95	<0.005	0.7	7.0	4.6	57	<0.1	3.7	7.1	601	2.62	2.4	<0.5	18.1	34	<0.1	0.1	<0.1	24	0.88
1456883	Rock	2.01	<0.005	0.6	5.3	35.8	58	<0.1	3.4	7.8	564	2.50	1.6	<0.5	18.7	45	0.3	<0.1	0.5	24	0.81
1456884	Rock	1.14	<0.005	1.3	4.9	6.7	105	<0.1	6.7	13.0	1166	4.10	6.7	<0.5	16.2	79	0.2	0.1	<0.1	56	2.52
1456885	Rock	2.80	<0.005	1.0	11.3	8.8	60	<0.1	4.3	6.8	511	2.23	1.6	<0.5	16.1	53	<0.1	<0.1	0.1	22	0.92
1456886	Rock	1.60	<0.005	0.9	7.0	7.2	72	<0.1	4.1	8.1	532	2.51	2.2	61.1	21.1	58	<0.1	0.1	<0.1	24	0.87
1456887	Rock	3.32	<0.005	0.7	9.6	12.1	59	<0.1	5.3	6.5	454	2.31	2.7	<0.5	14.5	62	0.1	0.1	<0.1	24	1.11
1456888	Rock	3.35	<0.005	1.0	9.3	19.6	84	<0.1	8.6	7.9	645	2.71	3.5	<0.5	17.3	83	0.4	0.2	0.2	44	1.75



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

Method Analyte	Unit	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
MDL		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm		
1456859	Rock	0.050	42	9	0.41	270	0.038	<20	0.89	0.033	0.35	0.3	<0.01	4.4	0.1	<0.05	5	<0.5	<0.2	
1456860	Rock	0.050	43	9	0.41	292	0.038	<20	0.89	0.039	0.36	0.3	<0.01	4.2	0.1	<0.05	5	<0.5	<0.2	
1456861	Rock	0.054	37	23	0.46	126	0.045	<20	0.82	0.036	0.30	0.5	<0.01	5.1	0.1	<0.05	5	<0.5	<0.2	
1456862	Rock	0.048	39	28	0.42	191	0.018	<20	0.74	0.035	0.20	0.4	0.02	5.5	<0.1	<0.05	4	<0.5	<0.2	
1456863	Rock	0.055	48	10	0.44	89	0.020	<20	0.86	0.037	0.24	0.2	<0.01	4.2	<0.1	<0.05	5	<0.5	<0.2	
1456864	Rock	0.052	48	9	0.48	99	0.016	<20	0.86	0.029	0.22	0.2	<0.01	3.5	<0.1	<0.05	5	<0.5	<0.2	
1456865	Rock	0.055	48	10	0.42	92	0.018	<20	0.82	0.037	0.25	0.2	<0.01	4.1	<0.1	<0.05	5	<0.5	<0.2	
1456866	Rock	0.056	39	7	0.14	97	0.005	<20	0.64	0.027	0.24	0.4	0.03	3.5	0.1	<0.05	2	<0.5	<0.2	
1456867	Rock	0.059	35	7	0.19	113	0.004	<20	0.82	0.021	0.30	0.3	0.02	3.4	0.1	<0.05	3	<0.5	<0.2	
1456868	Rock	0.072	45	7	0.18	180	0.005	<20	0.73	0.026	0.26	0.4	0.02	4.1	<0.1	<0.05	2	<0.5	<0.2	
1456869	Rock	0.162	32	5	0.31	264	0.003	<20	0.98	0.019	0.30	0.3	0.02	5.4	<0.1	0.11	3	<0.5	<0.2	
1456870	Rock Pulp	0.064	4	33	0.74	102	0.122	<20	1.51	0.085	0.13	10.0	0.04	4.9	<0.1	<0.05	5	<0.5	<0.2	
1456871	Rock	0.071	38	4	0.28	344	0.001	<20	0.82	0.013	0.22	0.2	0.03	4.1	<0.1	0.25	2	<0.5	<0.2	
1456872	Rock	0.058	44	4	0.17	95	<0.001	<20	0.67	0.005	0.27	0.3	0.04	3.7	<0.1	0.17	2	<0.5	0.5	
1456873	Rock	0.054	33	10	0.08	665	<0.001	<20	0.37	0.003	0.20	0.3	0.09	4.2	<0.1	0.37	1	1.6	3.0	
1456874	Rock	0.047	27	8	0.44	351	<0.001	<20	0.42	0.005	0.26	0.4	0.05	3.4	<0.1	1.16	1	2.1	2.0	
1456875	Rock	0.048	24	6	0.75	235	<0.001	<20	0.44	0.009	0.28	0.4	0.03	4.0	0.1	0.63	1	<0.5	0.7	
1456876	Rock	0.057	28	23	0.84	375	0.001	<20	0.48	0.011	0.28	0.5	0.04	5.3	<0.1	0.87	2	<0.5	1.3	
1456877	Rock	0.065	26	29	0.79	83	0.001	<20	0.27	0.013	0.21	1.7	0.07	5.6	0.1	2.86	1	1.3	4.6	
1456878	Rock	0.053	35	12	0.55	262	0.002	<20	0.37	0.010	0.22	3.0	0.05	4.4	0.1	1.79	1	1.0	1.8	
1456879	Rock	0.040	39	6	0.34	101	0.036	<20	0.95	0.031	0.35	0.3	0.03	3.2	0.1	<0.05	5	<0.5	<0.2	
1456880	Rock Pulp	0.059	4	31	0.79	97	0.144	<20	1.60	0.082	0.13	12.3	0.01	4.6	<0.1	<0.05	5	<0.5	<0.2	
1456881	Rock	0.040	39	8	0.50	111	0.055	<20	1.03	0.036	0.38	0.4	0.01	4.0	0.1	<0.05	6	<0.5	<0.2	
1456882	Rock	0.037	45	8	0.60	112	0.081	<20	1.09	0.032	0.52	0.5	0.01	3.7	0.2	<0.05	5	<0.5	<0.2	
1456883	Rock	0.041	49	7	0.57	118	0.104	<20	1.14	0.036	0.66	0.3	<0.01	2.7	0.3	<0.05	6	<0.5	<0.2	
1456884	Rock	0.073	53	13	1.25	186	0.139	<20	1.90	0.030	0.69	0.3	0.01	8.6	0.2	<0.05	11	<0.5	<0.2	
1456885	Rock	0.039	46	8	0.48	115	0.072	<20	0.94	0.043	0.46	0.8	<0.01	2.6	0.2	<0.05	5	<0.5	<0.2	
1456886	Rock	0.052	49	10	0.59	126	0.069	<20	1.07	0.037	0.42	0.8	<0.01	2.7	0.2	<0.05	6	<0.5	<0.2	
1456887	Rock	0.045	41	12	0.52	113	0.055	<20	0.95	0.044	0.36	0.4	<0.01	2.9	0.1	<0.05	5	<0.5	<0.2	
1456888	Rock	0.054	47	20	0.71	133	0.080	<20	1.04	0.039	0.47	0.3	<0.01	6.9	0.2	<0.05	7	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 3 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1456889	Rock	3.03	0.009	1.7	14.1	29.3	68	<0.1	5.4	6.4	460	2.38	5.8	2.7	13.6	71	0.4	0.2	0.2	35	1.28
1456890	Rock	1.57	0.009	1.4	13.3	27.8	65	<0.1	4.8	5.8	426	2.20	5.4	3.6	12.6	63	0.3	0.2	0.2	34	1.14
1456891	Rock	4.19	<0.005	0.6	7.8	13.8	52	<0.1	3.2	5.6	414	2.13	3.5	<0.5	14.9	55	0.2	0.1	0.1	24	0.95
1456892	Rock	3.71	<0.005	0.9	9.1	10.9	55	<0.1	3.8	6.4	448	2.14	5.1	<0.5	17.9	47	0.2	0.1	<0.1	20	1.01
1456893	Rock	4.07	0.006	1.1	8.3	13.4	56	<0.1	3.6	7.5	510	2.35	5.1	<0.5	18.4	49	0.3	0.1	0.2	21	1.02
1456894	Rock	3.17	<0.005	0.9	10.6	8.5	61	<0.1	4.8	8.0	581	2.66	2.7	<0.5	19.5	71	<0.1	0.2	0.2	25	1.18
1456895	Rock	3.75	<0.005	0.6	10.3	15.2	59	<0.1	3.8	7.3	482	2.47	3.1	<0.5	20.2	59	0.2	0.1	0.1	22	1.02
1456896	Rock	3.26	0.013	1.6	12.0	27.0	64	<0.1	3.9	7.6	499	2.56	28.6	6.4	18.8	37	0.3	0.2	<0.1	20	0.68
1456897	Rock	0.88	0.051	3.4	11.3	36.4	72	0.2	5.4	10.2	804	3.13	112.9	41.2	22.1	38	0.6	0.3	0.2	20	0.69
1456898	Rock	2.11	0.017	6.6	17.8	17.9	61	0.1	4.8	8.2	779	2.51	8.6	10.8	17.7	17	0.2	0.2	0.5	21	0.23
1456899	Rock	3.58	0.011	5.2	12.9	9.8	67	0.1	5.2	7.4	528	2.42	9.5	2.6	18.5	18	<0.1	<0.1	0.2	19	0.27
1456900	Rock Pulp	0.13	2.394	67.6	2237.4	1313.3	4018	26.8	180.4	20.7	670	5.45	1242.6	750.5	3.0	86	22.7	18.0	11.3	56	1.62
1456901	Rock	4.18	0.006	3.3	11.8	13.4	54	<0.1	4.7	7.4	536	2.34	3.2	<0.5	17.0	46	0.1	0.1	0.3	21	0.97
1456902	Rock	2.10	<0.005	1.4	5.6	4.5	67	<0.1	4.8	9.2	689	2.83	3.4	0.7	17.1	50	<0.1	<0.1	<0.1	31	1.35
1456903	Rock	4.94	0.009	1.1	12.6	8.1	57	<0.1	4.7	7.8	492	2.48	2.2	0.5	17.9	33	<0.1	<0.1	0.1	24	0.74
1456904	Rock	3.83	<0.005	1.3	8.8	8.7	54	<0.1	5.8	7.2	589	2.29	2.5	<0.5	17.0	61	0.1	0.1	<0.1	21	1.67
1456905	Rock	1.35	<0.005	0.7	9.5	5.2	73	<0.1	4.0	8.4	595	2.63	2.4	8.4	16.4	43	<0.1	<0.1	<0.1	27	1.06
1456906	Rock	2.86	0.007	1.0	11.3	7.6	64	<0.1	4.7	8.0	674	2.65	5.9	2.3	17.4	65	<0.1	<0.1	0.2	27	1.65
1456907	Rock	3.34	<0.005	0.9	8.5	6.1	51	<0.1	3.7	7.2	480	2.28	3.2	2.8	19.2	32	0.2	<0.1	0.1	20	0.79
1456908	Rock	3.79	<0.005	0.8	10.6	6.0	57	<0.1	3.9	7.9	547	2.53	5.4	1.6	19.4	39	0.1	<0.1	<0.1	24	0.84
1456909	Rock	3.40	<0.005	1.1	9.5	8.4	60	<0.1	4.0	8.1	592	2.49	1.9	1.2	18.2	55	0.2	<0.1	0.1	26	1.25
1456910	Rock Pulp	0.13	0.860	4.4	35.8	5.6	54	0.2	26.1	10.1	410	2.60	7.5	534.9	0.9	40	0.2	0.9	0.1	60	0.86
1456911	Rock	2.85	<0.005	0.8	8.4	5.6	55	<0.1	3.8	7.7	547	2.49	2.0	1.5	17.7	39	<0.1	<0.1	<0.1	25	0.94
1456912	Rock	3.20	0.006	1.4	12.1	8.0	72	<0.1	3.4	7.9	757	2.75	8.8	3.5	12.4	69	0.1	<0.1	0.1	34	1.68
1456913	Rock	2.96	<0.005	1.5	12.6	15.2	76	0.1	2.9	7.4	655	2.96	9.8	2.5	8.4	109	0.3	<0.1	0.2	44	2.12
1456914	Rock	4.00	<0.005	1.5	11.0	16.2	83	<0.1	4.9	9.0	697	2.89	4.9	2.1	18.2	39	0.6	<0.1	0.2	28	1.74
1456915	Rock	3.90	0.012	1.8	20.7	69.2	92	0.3	10.2	10.7	753	3.29	17.6	11.5	11.3	51	0.7	0.1	1.3	44	1.31
1456916	Rock	4.12	<0.005	0.7	7.8	6.0	60	<0.1	4.3	8.4	543	2.63	2.4	1.8	17.3	40	<0.1	<0.1	0.1	26	0.81
1456917	Rock	1.71	0.006	0.9	5.2	4.9	66	<0.1	4.3	8.2	534	2.65	5.1	4.9	17.4	32	<0.1	<0.1	<0.1	28	0.57
1456918	Rock	2.23	<0.005	0.9	11.7	5.6	66	0.2	4.1	8.3	559	2.62	1.7	5.0	15.5	32	<0.1	<0.1	<0.1	30	0.55



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1456889	Rock	0.041	34	15	0.48	134	0.068	<20	1.02	0.040	0.43	0.4	<0.01	4.4	0.2	<0.05	5	<0.5	<0.2
1456890	Rock	0.042	31	13	0.44	121	0.062	<20	0.94	0.032	0.39	0.3	0.01	4.6	0.2	<0.05	5	<0.5	<0.2
1456891	Rock	0.045	38	9	0.42	122	0.067	<20	0.97	0.040	0.48	0.3	<0.01	3.1	0.2	<0.05	5	<0.5	<0.2
1456892	Rock	0.045	46	9	0.42	122	0.060	<20	0.96	0.034	0.49	0.3	<0.01	3.4	0.2	<0.05	5	<0.5	<0.2
1456893	Rock	0.047	45	8	0.42	147	0.066	<20	1.01	0.028	0.54	0.4	<0.01	3.3	0.2	<0.05	5	<0.5	<0.2
1456894	Rock	0.055	51	12	0.55	149	0.090	<20	1.16	0.033	0.69	0.3	<0.01	3.5	0.3	<0.05	6	<0.5	<0.2
1456895	Rock	0.049	52	9	0.51	138	0.072	<20	1.16	0.025	0.66	0.2	<0.01	3.0	0.3	<0.05	6	<0.5	<0.2
1456896	Rock	0.047	38	9	0.42	160	0.040	<20	1.12	0.019	0.54	0.3	0.01	3.1	0.2	<0.05	5	<0.5	<0.2
1456897	Rock	0.066	43	11	0.36	184	0.021	<20	1.13	0.017	0.54	0.7	0.02	4.4	0.2	<0.05	4	<0.5	0.6
1456898	Rock	0.043	48	8	0.42	144	0.039	<20	1.13	0.025	0.43	0.4	0.02	4.0	0.2	<0.05	5	<0.5	<0.2
1456899	Rock	0.044	46	7	0.44	117	0.043	<20	1.04	0.026	0.38	0.5	0.01	4.0	0.1	<0.05	5	<0.5	<0.2
1456900	Rock Pulp	0.060	12	47	0.88	259	0.101	<20	1.53	0.083	0.20	8.9	0.76	4.5	1.3	1.53	6	3.4	0.5
1456901	Rock	0.041	47	8	0.42	114	0.048	<20	0.94	0.038	0.45	0.4	<0.01	3.7	0.2	<0.05	5	<0.5	<0.2
1456902	Rock	0.048	46	10	0.72	111	0.072	<20	1.24	0.038	0.52	0.4	0.01	5.2	0.2	<0.05	6	<0.5	<0.2
1456903	Rock	0.043	49	9	0.47	114	0.057	<20	1.05	0.036	0.47	0.3	0.02	3.7	0.2	<0.05	6	<0.5	<0.2
1456904	Rock	0.045	50	9	0.48	100	0.048	<20	0.95	0.030	0.42	0.3	0.02	3.4	0.2	<0.05	6	<0.5	<0.2
1456905	Rock	0.044	44	9	0.73	113	0.082	<20	1.23	0.035	0.56	0.2	0.05	4.3	0.2	<0.05	6	<0.5	0.2
1456906	Rock	0.050	50	10	0.53	131	0.043	<20	1.09	0.036	0.37	0.2	<0.01	4.8	0.2	<0.05	6	<0.5	<0.2
1456907	Rock	0.046	53	8	0.45	117	0.044	<20	1.02	0.028	0.38	0.1	<0.01	3.9	0.2	<0.05	6	<0.5	<0.2
1456908	Rock	0.052	50	9	0.44	125	0.062	<20	1.05	0.033	0.50	0.2	<0.01	3.9	0.2	<0.05	6	<0.5	<0.2
1456909	Rock	0.053	45	10	0.51	129	0.070	<20	1.02	0.036	0.52	0.2	<0.01	4.0	0.2	<0.05	6	<0.5	<0.2
1456910	Rock Pulp	0.063	5	36	0.76	102	0.132	<20	1.57	0.091	0.14	11.0	0.05	5.2	<0.1	<0.05	5	<0.5	<0.2
1456911	Rock	0.052	45	10	0.55	122	0.087	<20	1.12	0.037	0.65	0.2	<0.01	3.7	0.3	<0.05	6	<0.5	<0.2
1456912	Rock	0.091	38	10	0.55	164	0.066	<20	1.15	0.038	0.55	0.2	<0.01	5.3	0.2	<0.05	6	<0.5	<0.2
1456913	Rock	0.127	31	9	0.44	200	0.054	<20	1.00	0.050	0.39	0.2	<0.01	6.8	0.1	<0.05	6	<0.5	<0.2
1456914	Rock	0.056	52	11	0.58	191	0.086	<20	1.17	0.029	0.63	0.3	<0.01	5.2	0.3	<0.05	6	<0.5	<0.2
1456915	Rock	0.065	34	41	0.69	203	0.087	<20	1.17	0.039	0.65	0.4	<0.01	8.3	0.3	<0.05	6	<0.5	0.3
1456916	Rock	0.052	45	11	0.60	156	0.111	<20	1.16	0.035	0.74	0.3	<0.01	2.8	0.3	<0.05	6	<0.5	<0.2
1456917	Rock	0.052	44	13	0.61	167	0.126	<20	1.18	0.039	0.76	0.5	<0.01	2.7	0.3	<0.05	6	<0.5	<0.2
1456918	Rock	0.058	39	12	0.68	163	0.144	<20	1.19	0.044	0.80	0.5	<0.01	3.3	0.3	<0.05	6	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 4 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1456919	Rock	2.25	0.009	1.3	12.5	7.0	54	<0.1	4.0	8.3	557	2.63	5.6	8.1	14.6	31	<0.1	0.1	<0.1	28	0.51	
1456920	Rock Pulp	0.12	<0.005	2.6	26.8	2.5	46	0.2	24.9	11.2	417	2.46	4.9	<0.5	1.0	39	0.2	0.3	<0.1	59	0.84	
1456921	Rock	2.23	<0.005	1.1	8.7	5.6	62	<0.1	4.3	8.5	617	2.77	3.2	2.3	18.1	25	<0.1	0.1	<0.1	28	0.39	
1456922	Rock	2.41	0.007	1.2	7.9	5.6	63	<0.1	4.7	8.0	568	2.70	3.6	5.1	18.5	26	<0.1	<0.1	<0.1	28	0.34	
1456923	Rock	1.96	0.009	1.4	7.2	7.1	65	<0.1	4.2	8.6	590	2.58	4.3	6.6	17.6	23	0.1	0.1	0.3	26	0.24	
1456924	Rock	2.70	0.009	3.0	12.9	58.5	74	0.2	4.4	8.1	610	2.38	3.4	3.2	17.7	65	0.7	0.1	1.7	19	1.35	
1456925	Rock	3.35	0.015	1.5	9.6	9.8	57	0.1	4.1	8.3	595	2.55	12.3	11.2	18.0	50	0.2	0.2	0.2	23	1.38	
1456926	Rock	3.41	0.051	2.1	12.7	14.3	62	0.2	3.7	8.7	596	2.69	32.5	50.1	16.7	52	0.1	0.2	0.2	23	1.06	
1456927	Rock	3.28	0.014	2.1	11.8	9.6	60	<0.1	10.4	8.9	539	2.50	10.8	11.0	18.8	54	<0.1	0.2	0.1	21	0.97	
1456928	Rock	3.40	0.007	1.7	8.3	15.4	76	<0.1	43.9	11.9	708	2.85	4.4	3.9	15.9	95	0.1	0.2	0.2	32	2.39	
1456929	Rock	2.44	<0.005	1.1	7.5	8.3	56	<0.1	4.7	7.6	498	2.39	2.4	2.3	18.2	48	<0.1	<0.1	<0.1	21	0.91	
1456930	Rock	1.94	<0.005	1.0	7.9	9.0	54	<0.1	4.9	7.4	466	2.19	1.6	1.1	18.4	50	<0.1	<0.1	<0.1	19	1.01	
1456931	Rock	2.01	0.005	0.8	5.1	5.9	47	<0.1	3.0	6.0	581	2.02	3.4	4.2	14.4	68	<0.1	<0.1	<0.1	16	1.43	
1456932	Rock	2.15	0.035	1.7	6.8	11.6	42	0.2	3.0	6.4	654	1.94	18.4	33.4	15.9	60	<0.1	0.1	0.1	14	1.48	
1456933	Rock	2.29	0.034	1.3	8.5	10.9	40	0.2	3.0	5.3	452	1.69	17.1	31.3	14.7	49	<0.1	0.1	0.1	12	1.05	



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000429.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1456919	Rock	0.055	41	12	0.59	149	0.115	<20	1.20	0.038	0.78	0.4	<0.01	3.3	0.3	<0.05	5	<0.5	<0.2
1456920	Rock Pulp	0.064	5	34	0.79	101	0.132	<20	1.59	0.082	0.13	12.8	0.02	5.2	<0.1	<0.05	5	<0.5	<0.2
1456921	Rock	0.053	50	12	0.65	155	0.140	<20	1.37	0.033	0.92	0.4	<0.01	3.1	0.4	<0.05	6	<0.5	<0.2
1456922	Rock	0.054	47	13	0.63	152	0.129	<20	1.26	0.040	0.83	0.4	<0.01	3.8	0.3	<0.05	6	<0.5	<0.2
1456923	Rock	0.054	48	11	0.58	158	0.125	<20	1.25	0.028	0.82	0.4	<0.01	3.4	0.3	<0.05	6	<0.5	<0.2
1456924	Rock	0.056	50	10	0.49	219	0.068	<20	1.27	0.021	0.73	0.2	<0.01	3.2	0.3	<0.05	4	<0.5	<0.2
1456925	Rock	0.052	49	12	0.48	205	0.091	<20	1.04	0.029	0.67	0.3	<0.01	3.6	0.3	<0.05	5	<0.5	0.2
1456926	Rock	0.063	47	10	0.43	161	0.051	<20	0.99	0.036	0.53	0.3	0.03	3.8	0.2	<0.05	5	<0.5	0.4
1456927	Rock	0.054	47	18	0.49	248	0.049	<20	1.11	0.027	0.55	0.3	<0.01	3.9	0.3	<0.05	5	<0.5	<0.2
1456928	Rock	0.064	44	102	0.77	125	0.065	<20	1.26	0.024	0.57	0.2	<0.01	6.7	0.3	<0.05	6	<0.5	<0.2
1456929	Rock	0.047	43	11	0.49	80	0.060	<20	1.07	0.036	0.53	0.2	<0.01	4.0	0.2	<0.05	5	<0.5	<0.2
1456930	Rock	0.048	44	11	0.46	75	0.052	<20	1.01	0.028	0.49	0.2	<0.01	3.5	0.2	<0.05	5	<0.5	<0.2
1456931	Rock	0.041	39	6	0.41	70	0.052	<20	0.94	0.031	0.50	<0.1	<0.01	3.0	0.2	<0.05	5	<0.5	<0.2
1456932	Rock	0.040	38	6	0.35	85	0.038	<20	0.81	0.021	0.40	0.2	0.02	2.9	0.1	<0.05	4	<0.5	0.3
1456933	Rock	0.037	30	5	0.29	65	0.013	<20	0.71	0.020	0.29	<0.1	0.01	2.9	<0.1	<0.05	3	<0.5	0.2



QUALITY CONTROL REPORT

WHI16000429.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1456872	Rock	2.38	0.058	2.4	17.3	20.8	55	0.5	3.8	9.1	441	2.43	54.9	58.1	18.2	64	0.2	0.2	0.3	6	1.53
REP 1456872	QC	0.061																			
1456890	Rock	1.57	0.009	1.4	13.3	27.8	65	<0.1	4.8	5.8	426	2.20	5.4	3.6	12.6	63	0.3	0.2	0.2	34	1.14
REP 1456890	QC	1.3 13.2 27.3 64 <0.1 5.3 6.0 425 2.21 5.3 1.9 12.5 64 0.4 0.2 0.2 33 1.14																			
1456919	Rock	2.25	0.009	1.3	12.5	7.0	54	<0.1	4.0	8.3	557	2.63	5.6	8.1	14.6	31	<0.1	0.1	<0.1	28	0.51
REP 1456919	QC	0.008																			
1456920	Rock Pulp	0.12	<0.005	2.6	26.8	2.5	46	0.2	24.9	11.2	417	2.46	4.9	<0.5	1.0	39	0.2	0.3	<0.1	59	0.84
REP 1456920	QC	2.6 26.2 2.5 45 0.2 24.9 11.0 422 2.51 5.0 <0.5 1.0 39 0.2 0.3 <0.1 59 0.84																			
Core Reject Duplicates																					
1456904	Rock	3.83	<0.005	1.3	8.8	8.7	54	<0.1	5.8	7.2	589	2.29	2.5	<0.5	17.0	61	0.1	0.1	<0.1	21	1.67
DUP 1456904	QC	<0.005 1.2 7.9 8.6 50 <0.1 5.6 7.4 572 2.33 2.1 2.1 17.2 60 <0.1 0.1 <0.1 21 1.63																			
Reference Materials																					
STD DS10	Standard	15.7 163.2 158.2 378 2.0 78.5 13.3 958 2.91 49.9 95.0 8.5 73 2.8 9.2 13.9 44 1.12																			
STD DS10	Standard	14.4 160.0 145.5 367 2.0 78.5 14.0 921 2.83 46.9 57.2 7.9 67 2.7 8.0 12.6 43 1.08																			
STD DS10	Standard	14.1 163.9 156.7 371 2.1 77.3 14.7 897 2.78 49.5 66.5 7.9 69 3.0 8.1 13.6 43 1.07																			
STD OREAS45EA	Standard	1.7 743.2 16.3 34 0.3 420.6 56.8 453 22.43 12.5 57.7 12.3 5 <0.1 0.4 0.3 337 0.03																			
STD OREAS45EA	Standard	1.8 729.9 14.4 31 0.3 413.3 57.7 448 22.49 10.5 60.7 9.6 4 <0.1 0.3 0.3 336 0.03																			
STD OREAS45EA	Standard	1.7 706.7 14.1 31 0.3 399.5 56.6 420 21.94 10.6 48.3 9.9 4 <0.1 0.3 0.3 309 0.03																			
STD OXC145	Standard	0.223																			
STD OXC145	Standard	0.213																			
STD OXC145	Standard	0.212																			
STD OXH122	Standard	1.271																			
STD OXH122	Standard	1.257																			
STD OXH122	Standard	1.221																			
STD OXN117	Standard	7.990																			
STD OXN117	Standard	7.848																			
STD OXN117	Standard	7.479																			
STD DS10 Expected		13.6 154.61 150.55 370 2.02 74.6 12.9 875 2.7188 46.2 91.9 7.5 67.1 2.62 9 11.65 43 1.0625																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000429.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1456872	Rock	0.058	44	4	0.17	95	<20	0.67	0.005	0.27	0.3	0.04	3.7	<0.1	0.17	2	<0.5	0.5	
REP 1456872	QC																		
1456890	Rock	0.042	31	13	0.44	121	0.062	<20	0.94	0.032	0.39	0.3	0.01	4.6	0.2	<0.05	5	<0.5	<0.2
REP 1456890	QC	0.044	34	13	0.45	123	0.065	<20	0.97	0.034	0.41	0.4	<0.01	4.1	0.2	<0.05	5	<0.5	<0.2
1456919	Rock	0.055	41	12	0.59	149	0.115	<20	1.20	0.038	0.78	0.4	<0.01	3.3	0.3	<0.05	5	<0.5	<0.2
REP 1456919	QC																		
1456920	Rock Pulp	0.064	5	34	0.79	101	0.132	<20	1.59	0.082	0.13	12.8	0.02	5.2	<0.1	<0.05	5	<0.5	<0.2
REP 1456920	QC	0.066	5	34	0.80	100	0.129	<20	1.62	0.082	0.14	12.0	0.02	5.3	<0.1	<0.05	5	<0.5	<0.2
Core Reject Duplicates																			
1456904	Rock	0.045	50	9	0.48	100	0.048	<20	0.95	0.030	0.42	0.3	0.02	3.4	0.2	<0.05	6	<0.5	<0.2
DUP 1456904	QC	0.042	47	10	0.47	101	0.046	<20	0.96	0.034	0.42	0.3	0.03	3.3	0.1	<0.05	6	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.085	19	58	0.82	450	0.093	<20	1.10	0.075	0.36	3.1	0.37	3.0	5.7	0.28	5	1.7	5.0
STD DS10	Standard	0.082	19	60	0.80	419	0.082	<20	1.05	0.071	0.35	3.9	0.28	3.2	5.2	0.28	4	2.2	4.7
STD DS10	Standard	0.087	18	58	0.80	438	0.080	<20	1.05	0.072	0.34	3.1	0.27	3.2	5.3	0.29	4	2.0	5.0
STD OREAS45EA	Standard	0.029	8	860	0.10	149	0.110	<20	2.89	0.023	0.05	<0.1	0.02	81.4	<0.1	<0.05	14	1.0	<0.2
STD OREAS45EA	Standard	0.029	8	908	0.09	161	0.099	<20	3.32	0.024	0.05	<0.1	0.01	82.3	<0.1	<0.05	13	0.8	<0.2
STD OREAS45EA	Standard	0.029	8	863	0.09	155	0.096	<20	3.26	0.025	0.06	<0.1	0.01	80.7	<0.1	<0.05	12	0.9	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH122	Standard																		
STD OXH122	Standard																		
STD OXH122	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000429.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
STD OXN117 Expected			7.679																			
STD OXC145 Expected			0.212																			
STD OXH122 Expected			1.247																			
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank		<0.005																			
BLK	Blank		0.013																			
Prep Wash																						
ROCK-WHI	Prep Blank		<0.005	0.7	3.3	1.4	31	<0.1	0.7	3.9	415	1.71	0.9	<0.5	2.6	24	<0.1	<0.1	<0.1	23	0.57	
ROCK-WHI	Prep Blank		<0.005	0.7	3.4	1.4	29	<0.1	0.7	3.8	416	1.76	0.8	<0.5	2.5	26	<0.1	<0.1	<0.1	23	0.59	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: November 25, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000429.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
STD OXN117 Expected																				
STD OXC145 Expected																				
STD OXH122 Expected																				
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank																			
BLK	Blank																			
Prep Wash																				
ROCK-WHI	Prep Blank	0.045	5	3	0.40	64	0.082	<20	0.89	0.089	0.10	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.046	5	4	0.39	74	0.084	<20	0.91	0.103	0.10	0.1	<0.01	2.6	<0.1	<0.05	4	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 16, 2016
Report Date: December 09, 2016
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI16000438.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-11-15-Rock-RAB
P.O. Number
Number of Samples: 35

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	32	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	35	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	35	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	35	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	35	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 2 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000438.1

Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1464007	Rock	2.51	0.037	3.4	17.7	9.3	18	0.3	2.4	3.3	341	1.35	3.0	30.1	1.8	42	<0.1	0.1	<0.1	6	1.32
1464008	Rock	2.82	0.130	2.4	13.3	16.8	34	1.2	1.9	4.5	417	1.80	5.4	142.9	7.4	36	0.4	0.1	0.2	8	1.45
1464009	Rock	1.95	0.096	2.2	14.8	57.7	58	1.0	2.3	5.2	378	1.82	5.7	91.0	4.3	44	0.5	0.1	0.9	10	1.48
1464010	Rock Pulp	0.12	0.829	4.2	33.5	5.4	52	0.3	24.5	9.3	402	2.50	6.9	607.3	1.0	38	0.2	0.8	0.1	61	0.85
1464011	Rock	2.92	0.056	1.7	14.8	9.6	35	0.4	3.1	5.6	355	1.78	4.4	52.2	5.1	38	<0.1	0.1	0.2	10	1.62
1464012	Rock	3.24	0.053	3.0	9.9	8.3	20	0.3	2.2	3.6	388	1.47	3.7	46.6	5.2	30	<0.1	<0.1	<0.1	8	1.60
1464013	Rock	3.48	0.139	2.4	9.0	6.6	18	0.6	1.5	4.1	329	1.41	5.1	124.6	5.3	41	<0.1	0.1	<0.1	6	1.63
1464014	Rock	1.94	0.129	2.3	9.1	6.8	16	0.6	1.6	3.9	433	1.51	4.9	128.7	7.1	33	<0.1	0.1	<0.1	5	1.72
1464015	Rock	3.42	0.114	3.5	11.6	9.2	41	1.4	2.7	6.0	451	2.22	6.7	115.8	5.8	35	0.1	0.2	0.2	8	2.17
1464016	Rock	3.53	0.138	4.3	14.4	11.8	103	2.3	3.1	6.6	450	3.15	8.7	139.0	2.4	28	0.6	0.3	0.4	7	1.86
1464017	Rock	3.26	0.228	1.7	17.1	8.5	102	1.5	5.2	12.4	571	3.56	12.2	228.6	2.5	45	0.1	0.3	0.1	25	1.44
1464018	Rock	2.87	0.318	3.0	16.7	5.8	97	1.2	2.4	4.5	586	2.46	10.5	311.4	2.6	42	0.1	0.2	0.1	11	1.33
1464019	Rock	2.20	0.178	2.5	17.1	7.9	112	1.0	2.1	4.4	583	2.65	8.4	186.2	3.5	39	0.3	0.2	0.1	10	1.71
1464020	Rock Pulp	0.12	<0.005	2.4	25.5	2.6	46	0.4	23.8	10.3	407	2.40	4.8	2.2	1.0	39	0.2	0.2	<0.1	61	0.85
1464021	Rock	2.53	0.253	2.1	14.1	6.5	126	1.2	2.7	4.4	560	2.44	12.7	208.2	2.8	40	0.3	0.2	0.1	12	1.42
1464022	Rock	3.56	0.217	2.2	19.8	9.5	144	2.1	3.9	4.7	625	2.55	9.7	206.4	3.4	40	0.3	0.3	0.1	8	1.98
1464023	Rock	3.03	0.129	2.2	16.7	16.4	89	1.8	3.4	6.1	752	2.54	12.1	141.2	3.7	66	0.3	0.3	0.3	11	2.42
1464024	Rock	2.87	0.191	8.6	49.0	23.3	76	2.2	5.3	7.7	840	3.00	30.6	200.5	2.2	67	0.2	0.6	0.4	11	2.53
1464025	Rock	3.01	0.057	12.4	97.6	22.3	80	3.0	5.0	9.0	859	3.55	12.2	52.0	1.9	50	0.6	0.9	0.4	8	2.37
1464026	Rock	2.87	0.022	8.6	289.8	20.8	90	4.6	2.6	4.2	644	2.09	4.7	21.6	1.3	70	1.3	0.6	0.4	4	2.20
1464027	Rock	3.09	0.016	3.0	337.9	25.5	73	4.1	1.6	1.7	192	1.34	1.9	14.5	0.9	121	1.5	0.3	0.4	2	0.69
1464028	Rock	2.66	0.019	3.1	294.8	23.4	64	4.2	1.3	2.2	267	1.63	2.5	16.5	1.2	1916	1.4	0.4	0.6	2	0.96
1464029	Rock	2.70	0.020	7.7	215.2	20.8	55	3.7	1.9	3.3	308	2.21	3.7	22.4	1.5	427	1.1	0.5	0.6	3	0.84
1464030	Rock	2.69	0.020	7.8	223.8	22.6	59	3.9	2.4	3.7	336	2.28	3.8	17.5	1.6	349	1.2	0.5	0.6	3	0.84
1464031	Rock	2.58	0.021	7.6	430.8	40.1	92	6.1	2.0	2.9	408	1.91	3.1	17.1	1.1	339	2.3	0.4	1.3	2	0.99
1464032	Rock	1.58	0.018	10.8	386.9	50.3	89	5.2	2.1	4.0	456	2.02	3.0	14.9	1.1	280	2.2	0.4	1.3	3	1.30
1464033	Rock	2.44	0.023	19.8	398.9	39.7	79	4.1	2.3	3.4	695	2.09	4.5	23.0	1.3	271	2.1	0.5	1.2	4	1.90
1464034	Rock	3.52	0.060	3.4	60.4	19.7	42	1.8	4.5	9.0	872	3.27	14.5	54.8	2.0	173	0.1	0.6	0.4	18	2.04
1464035	Rock	2.61	0.046	8.6	35.1	10.5	41	1.0	4.1	7.1	692	2.45	6.9	49.8	5.6	990	<0.1	0.3	0.1	24	1.73
1464036	Rock	2.42	0.046	43.5	20.8	12.0	29	0.7	3.4	5.4	576	2.04	7.5	41.3	5.0	852	<0.1	0.3	0.2	20	1.47



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 2 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000438.1

Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Hg ppm	Sc ppm	Tl ppm	S %	Ga ppm	Se ppm	Te ppm	
1464007	Rock	0.029	4	12	0.21	484	<0.001	<20	0.26	0.021	0.22	1.1	0.02	1.4	<0.1	0.49	<1	<0.5	0.6
1464008	Rock	0.032	14	10	0.35	258	<0.001	<20	0.27	0.014	0.23	1.0	0.04	3.1	<0.1	0.74	<1	<0.5	1.6
1464009	Rock	0.049	13	11	0.28	232	<0.001	<20	0.30	0.026	0.26	1.3	0.04	2.4	<0.1	0.80	<1	0.8	1.3
1464010	Rock Pulp	0.056	4	34	0.74	100	0.129	<20	1.57	0.086	0.13	10.4	0.04	4.8	<0.1	<0.05	5	<0.5	<0.2
1464011	Rock	0.066	16	9	0.22	156	<0.001	<20	0.33	0.026	0.28	0.8	0.03	2.2	<0.1	0.66	1	<0.5	0.8
1464012	Rock	0.041	10	9	0.36	102	<0.001	<20	0.32	0.023	0.28	1.0	0.06	2.0	<0.1	0.51	<1	<0.5	0.6
1464013	Rock	0.028	12	9	0.29	483	<0.001	<20	0.24	0.013	0.22	1.4	0.02	1.9	<0.1	0.71	<1	<0.5	1.2
1464014	Rock	0.027	17	9	0.29	346	<0.001	<20	0.23	0.006	0.22	1.2	0.02	2.3	<0.1	0.71	<1	<0.5	1.0
1464015	Rock	0.034	16	10	0.24	166	<0.001	<20	0.19	0.003	0.18	2.3	0.06	5.0	<0.1	1.86	<1	1.0	2.0
1464016	Rock	0.043	10	11	0.26	111	<0.001	<20	0.19	0.003	0.18	2.1	0.06	6.1	<0.1	2.98	<1	1.7	2.4
1464017	Rock	0.070	12	11	0.56	130	<0.001	<20	0.61	0.003	0.26	1.4	0.07	8.1	<0.1	2.16	3	0.8	2.2
1464018	Rock	0.041	12	11	0.50	230	<0.001	<20	0.39	0.007	0.24	1.8	0.08	5.0	<0.1	1.52	2	<0.5	2.7
1464019	Rock	0.041	15	12	0.33	158	<0.001	<20	0.31	0.003	0.21	2.9	0.05	5.9	<0.1	2.22	2	1.1	1.7
1464020	Rock Pulp	0.060	4	32	0.79	101	0.131	<20	1.60	0.079	0.13	12.8	0.01	5.0	<0.1	<0.05	5	<0.5	<0.2
1464021	Rock	0.040	13	11	0.34	147	<0.001	<20	0.32	0.003	0.21	2.3	0.04	6.4	<0.1	2.04	2	0.7	1.8
1464022	Rock	0.034	13	11	0.24	115	<0.001	<20	0.18	0.002	0.17	3.3	0.04	7.6	<0.1	2.53	<1	1.0	2.6
1464023	Rock	0.039	13	11	0.37	132	<0.001	<20	0.17	0.003	0.18	3.1	0.06	6.3	<0.1	2.48	<1	1.7	2.5
1464024	Rock	0.044	10	11	0.46	96	<0.001	<20	0.23	0.003	0.19	2.2	0.06	7.9	<0.1	2.83	<1	1.7	2.8
1464025	Rock	0.057	9	10	0.20	78	<0.001	<20	0.20	0.003	0.19	2.9	0.03	10.4	<0.1	3.79	<1	2.7	1.5
1464026	Rock	0.025	7	11	0.17	107	<0.001	<20	0.15	0.002	0.17	3.9	0.04	7.6	0.2	2.11	<1	1.6	1.3
1464027	Rock	0.011	5	12	0.04	256	<0.001	<20	0.15	0.003	0.20	3.6	0.03	2.2	<0.1	1.25	<1	1.0	1.1
1464028	Rock	0.015	6	13	0.04	156	<0.001	<20	0.16	0.003	0.19	3.7	0.02	2.8	<0.1	1.64	<1	1.2	1.2
1464029	Rock	0.017	9	14	0.06	123	<0.001	<20	0.16	0.003	0.20	4.9	0.02	3.7	<0.1	2.27	<1	1.5	1.2
1464030	Rock	0.018	9	13	0.07	142	<0.001	<20	0.16	0.003	0.20	5.5	0.02	3.8	<0.1	2.33	<1	1.6	1.3
1464031	Rock	0.011	8	13	0.06	163	<0.001	<20	0.16	0.003	0.20	7.0	0.03	3.6	<0.1	1.89	<1	1.4	1.7
1464032	Rock	0.015	7	12	0.05	121	<0.001	<20	0.13	0.002	0.16	6.9	0.03	4.7	<0.1	2.11	<1	1.6	1.5
1464033	Rock	0.018	9	11	0.14	153	<0.001	<20	0.17	0.003	0.21	6.5	0.02	5.9	<0.1	2.02	<1	1.4	1.5
1464034	Rock	0.058	9	13	0.48	97	<0.001	<20	0.30	0.004	0.20	3.1	0.03	8.2	<0.1	3.05	2	2.6	1.4
1464035	Rock	0.042	14	15	0.60	170	0.001	<20	0.43	0.013	0.20	2.5	0.03	5.3	<0.1	1.79	3	1.2	0.8
1464036	Rock	0.035	14	13	0.48	233	0.001	<20	0.40	0.020	0.20	2.8	0.03	3.9	<0.1	1.46	3	1.1	0.5



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 3 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000438.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1464037	Rock	2.94	0.083	2.9	44.2	16.5	56	1.5	4.5	10.6	1015	3.67	13.2	80.2	3.2	311	0.1	0.5	0.3	49	2.13
1464038	Rock	2.49	0.068	3.1	33.2	14.5	42	1.2	5.7	7.4	812	2.95	11.6	58.7	2.7	175	0.1	0.5	0.3	30	1.87
1464039	Rock	3.15	0.059	2.4	51.8	16.0	51	1.1	4.4	8.3	980	3.46	14.2	61.5	2.8	162	0.3	0.6	0.4	33	2.10
1464040	Rock Pulp	0.12	2.190	57.7	2185.6	1246.7	3609	26.0	175.9	18.9	616	4.99	1104.1	2507.3	2.7	73	20.5	16.8	10.2	54	1.47
1464041	Rock	3.33	0.070	5.5	82.4	21.9	53	1.8	5.2	7.9	797	3.47	18.4	78.9	2.9	108	0.2	0.7	0.4	27	1.69



BUREAU VERITAS
MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000438.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1464037	Rock	0.072	11	11	0.91	128	0.002	<20	0.65	0.008	0.22	1.4	0.08	9.7	<0.1	2.83	4	2.4	1.0
1464038	Rock	0.052	11	12	0.65	132	0.001	<20	0.48	0.008	0.21	1.9	0.05	7.0	<0.1	2.42	3	2.1	1.0
1464039	Rock	0.061	14	14	0.68	118	0.001	<20	0.48	0.007	0.19	2.5	0.07	7.7	<0.1	2.95	4	2.4	1.2
1464040	Rock Pulp	0.066	10	43	0.86	210	0.083	<20	1.43	0.077	0.18	8.5	0.69	4.1	1.2	1.49	5	3.4	0.5
1464041	Rock	0.066	13	15	0.63	95	0.001	<20	0.45	0.006	0.22	2.8	0.04	6.5	<0.1	3.14	3	2.6	1.4



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Project: QVV
Report Date: December 09, 2016

Page: 1 of 1 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000438.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
1464017	Rock	3.26	0.228	1.7	17.1	8.5	102	1.5	5.2	12.4	571	3.56	12.2	228.6	2.5	45	0.1	0.3	0.1	25	1.44
REP 1464017	QC			1.9	16.8	8.4	104	1.5	5.5	12.5	578	3.54	12.5	262.6	2.6	46	0.1	0.3	0.1	24	1.45
1464020	Rock Pulp	0.12	<0.005	2.4	25.5	2.6	46	0.4	23.8	10.3	407	2.40	4.8	2.2	1.0	39	0.2	0.2	<0.1	61	0.85
REP 1464020	QC		0.006																		
Core Reject Duplicates																					
1464034	Rock	3.52	0.060	3.4	60.4	19.7	42	1.8	4.5	9.0	872	3.27	14.5	54.8	2.0	173	0.1	0.6	0.4	18	2.04
DUP 1464034	QC		0.063	3.7	62.6	19.6	43	1.9	4.3	9.1	861	3.25	14.8	57.6	2.1	177	0.1	0.6	0.4	17	2.07
Reference Materials																					
STD DS10	Standard			14.2	162.0	161.0	373	1.8	78.2	14.1	903	2.75	49.0	59.7	7.9	68	2.7	9.2	13.4	43	1.12
STD DS10	Standard			14.7	153.4	159.3	371	2.3	76.1	13.2	897	2.78	47.5	89.8	8.0	68	2.9	8.2	13.5	44	1.08
STD OREAS45EA	Standard			1.7	719.5	15.4	32	0.2	408.7	54.2	434	21.34	12.2	53.3	11.0	4	<0.1	0.3	0.3	329	0.03
STD OREAS45EA	Standard			1.7	726.2	15.9	33	0.3	406.6	54.6	421	22.69	11.9	57.5	11.1	4	<0.1	0.3	0.3	308	0.03
STD OXC145	Standard		0.218																		
STD OXH122	Standard		1.236																		
STD OXN117	Standard		7.792																		
STD OXN117 Expected			7.679																		
STD OXC145 Expected			0.212																		
STD OXH122 Expected			1.247																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.6	3.4	4.4	30	<0.1	0.6	3.5	413	1.69	0.9	<0.5	2.4	23	<0.1	<0.1	<0.1	23	0.55
ROCK-WHI	Prep Blank		<0.005	0.8	3.3	2.5	29	<0.1	0.6	3.5	402	1.69	0.8	<0.5	2.3	22	<0.1	<0.1	<0.1	23	0.57



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 1 of 1 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000438.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
1464017	Rock	0.070	12	11	0.56	130	<0.001	<20	0.61	0.003	0.26	1.4	0.07	8.1	<0.1	2.16	3	0.8	2.2
REP 1464017	QC	0.074	12	12	0.56	117	<0.001	<20	0.61	0.003	0.26	1.3	0.07	8.0	<0.1	2.19	3	0.9	2.2
1464020	Rock Pulp	0.060	4	32	0.79	101	0.131	<20	1.60	0.079	0.13	12.8	0.01	5.0	<0.1	<0.05	5	<0.5	<0.2
REP 1464020	QC																		
Core Reject Duplicates																			
1464034	Rock	0.058	9	13	0.48	97	<0.001	<20	0.30	0.004	0.20	3.1	0.03	8.2	<0.1	3.05	2	2.6	1.4
DUP 1464034	QC	0.058	10	12	0.48	116	<0.001	<20	0.29	0.004	0.20	3.3	0.03	8.2	<0.1	3.06	2	2.4	1.4
Reference Materials																			
STD DS10	Standard	0.080	18	57	0.79	438	0.081	<20	1.05	0.070	0.34	3.1	0.28	3.0	5.4	0.28	4	2.2	5.0
STD DS10	Standard	0.080	18	58	0.80	429	0.082	<20	1.06	0.071	0.34	3.3	0.30	3.0	5.2	0.29	5	1.9	5.3
STD OREAS45EA	Standard	0.031	7	943	0.11	155	0.102	<20	3.24	0.021	0.05	<0.1	0.01	80.0	<0.1	<0.05	13	0.7	<0.2
STD OREAS45EA	Standard	0.032	7	921	0.11	159	0.101	<20	3.41	0.026	0.06	<0.1	<0.01	79.5	<0.1	<0.05	13	0.7	<0.2
STD OXC145	Standard																		
STD OXH122	Standard																		
STD OXN117	Standard																		
STD OXN117 Expected																			
STD OXC145 Expected																			
STD OXH122 Expected																			
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.039	5	2	0.39	66	0.077	<20	0.86	0.099	0.09	<0.1	<0.01	2.3	<0.1	<0.05	3	<0.5	<0.2
ROCK-WHI	Prep Blank	0.039	5	3	0.38	65	0.082	<20	0.91	0.106	0.10	0.1	<0.01	2.2	<0.1	<0.05	3	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 16, 2016
Report Date: December 09, 2016
Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000439.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-11-15-Rock-RAB
P.O. Number
Number of Samples: 10

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	9	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	10	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	10	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	10	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	10	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 2 of 2

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000439.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1464042	Rock	1.58	0.223	13.4	77.6	14.7	62	0.8	10.0	11.4	1035	3.68	14.9	205.9	2.5	52	0.2	4.0	0.4	30	0.38
1464043	Rock	2.29	0.037	18.9	151.9	25.8	96	1.4	6.0	7.2	329	4.79	34.6	33.6	1.4	50	0.2	17.5	0.7	17	0.08
1464044	Rock	2.19	0.063	8.4	180.2	24.6	77	2.6	12.1	11.8	280	4.21	23.4	54.5	1.4	15	<0.1	9.0	0.7	22	0.07
1464045	Rock	2.63	0.031	5.5	78.4	19.0	46	1.3	3.3	2.4	79	2.92	20.1	31.0	1.5	26	<0.1	6.2	0.7	9	0.05
1464046	Rock	1.46	0.034	3.5	126.7	11.7	59	0.6	3.6	5.6	151	4.14	14.1	33.0	1.2	32	<0.1	9.3	0.2	22	0.07
1464047	Rock	1.33	0.037	7.9	157.5	52.1	71	1.8	5.5	7.1	113	3.52	23.9	31.8	1.5	51	<0.1	9.5	0.7	12	0.05
1464048	Rock	2.32	0.041	5.3	209.3	80.2	102	1.6	13.1	19.2	2942	3.51	24.2	41.6	1.3	34	1.8	10.4	1.3	26	0.08
1464049	Rock	1.44	0.027	2.7	354.9	53.9	165	1.1	17.5	24.0	5993	3.69	7.7	28.6	0.9	27	4.9	3.1	0.6	48	0.14
1464050	Rock Pulp	0.12	<0.005	1.9	22.5	2.3	40	0.2	21.8	9.8	371	2.25	4.2	2.4	0.9	37	0.1	0.2	<0.1	56	0.76
1464051	Rock	0.87	0.058	5.3	569.9	78.0	128	2.6	12.0	23.8	4473	4.07	32.8	53.4	0.9	57	3.9	13.6	1.3	27	0.13



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 2 of 2

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000439.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.01	0.01	0.1	0.01	0.05	1	0.5	0.2
1464042	Rock	0.052	11	8	0.07	404	0.001	<20	0.40	0.006	0.20	0.3	0.08	11.2	<0.1	0.18	1	1.9	1.1
1464043	Rock	0.069	9	4	0.03	487	<0.001	<20	0.29	0.004	0.25	0.3	0.22	14.0	<0.1	0.24	<1	0.9	1.5
1464044	Rock	0.040	8	5	0.04	90	<0.001	<20	0.35	0.003	0.19	0.2	0.13	19.8	<0.1	<0.05	<1	1.4	2.2
1464045	Rock	0.044	8	4	0.02	530	<0.001	<20	0.19	0.003	0.22	0.7	0.16	7.3	<0.1	0.18	<1	1.2	1.3
1464046	Rock	0.065	5	6	0.02	229	<0.001	<20	0.23	0.009	0.21	0.4	0.15	8.6	<0.1	0.19	<1	1.3	1.0
1464047	Rock	0.039	6	3	0.02	429	<0.001	<20	0.21	0.009	0.28	0.3	0.19	7.5	<0.1	0.33	<1	1.8	1.5
1464048	Rock	0.025	7	7	0.06	428	0.002	<20	0.39	0.010	0.19	0.4	0.18	13.3	<0.1	0.10	<1	2.1	1.1
1464049	Rock	0.022	7	10	0.09	493	0.003	<20	0.68	0.016	0.21	0.2	0.12	22.6	0.1	<0.05	1	1.1	0.6
1464050	Rock Pulp	0.052	4	29	0.74	87	0.120	<20	1.43	0.074	0.13	10.8	0.01	4.6	<0.1	<0.05	5	0.6	<0.2
1464051	Rock	0.059	6	4	0.06	346	<0.001	<20	0.52	0.007	0.20	0.2	0.17	14.7	<0.1	0.10	<1	1.6	1.4



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 1 of 1 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000439.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Reference Materials																					
STD DS10 Standard			13.5	147.4	150.0	350	1.7	71.1	12.3	835	2.62	42.9	66.6	6.8	63	2.1	6.9	12.6	41	1.00	
STD OREAS45EA Standard			1.4	671.3	11.7	28	0.2	375.5	48.2	391	20.72	9.8	43.0	8.0	3	<0.1	0.3	0.2	284	0.03	
STD OXC145 Standard		0.212																			
STD OXH122 Standard		1.209																			
STD OXN117 Standard		7.711																			
STD OXN117 Expected		7.679																			
STD OXC145 Expected		0.212																			
STD OXH122 Expected		1.247																			
STD DS10 Expected			13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected			1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
BLK Blank		<0.005																			
BLK Blank		<0.005																			
BLK Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
Prep Wash																					
ROCK-WHI Prep Blank		<0.005	0.8	3.7	3.2	29	<0.1	1.0	3.8	400	1.69	0.8	4.1	2.3	24	<0.1	<0.1	<0.1	22	0.71	
ROCK-WHI Prep Blank		<0.005	0.7	6.0	5.5	29	<0.1	0.6	3.5	399	1.67	1.2	3.0	2.3	26	<0.1	<0.1	<0.1	21	0.54	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 09, 2016

Page: 1 of 1 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000439.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Reference Materials																			
STD DS10 Standard	0.070	17	53	0.75	385	0.075	<20	0.97	0.066	0.32	2.8	0.27	2.7	4.8	0.27	4	2.1	4.9	
STD OREAS45EA Standard	0.027	6	838	0.09	119	0.094	<20	3.14	0.021	0.05	<0.1	0.02	78.2	<0.1	<0.05	11	0.5	<0.2	
STD OXC145 Standard																			
STD OXH122 Standard																			
STD OXN117 Standard																			
STD OXN117 Expected																			
STD OXC145 Expected																			
STD OXH122 Expected																			
STD DS10 Expected	0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected	0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
BLK Blank																			
BLK Blank																			
BLK Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	0.7	<0.2	
Prep Wash																			
ROCK-WHI Prep Blank	0.039	5	3	0.38	66	0.074	<20	0.79	0.063	0.07	<0.1	<0.01	2.2	<0.1	<0.05	4	0.5	<0.2	
ROCK-WHI Prep Blank	0.037	5	3	0.37	66	0.080	<20	0.77	0.069	0.08	0.1	<0.01	2.4	<0.1	<0.05	3	<0.5	<0.2	



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Submitted By: David Terry
Receiving Lab: Canada-Whitehorse
Received: November 16, 2016
Report Date: December 10, 2016
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI16000440.1

CLIENT JOB INFORMATION

Project: QVV
Shipment ID: QVV2016-11-15-Rock-RAB
P.O. Number
Number of Samples: 80

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1
Canada

CC: Isaac Fage
Jodie Gibson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	75	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	80	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	80	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	80	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	80	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 2 of 4 Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1464052	Rock	1.66	0.046	16.6	96.1	22.4	60	0.7	4.9	5.2	357	2.97	23.7	42.1	2.2	29	<0.1	2.7	0.4	14	0.06
1464053	Rock	2.51	0.023	17.3	94.7	24.7	106	1.6	3.5	4.0	128	4.68	11.7	22.5	1.3	44	0.2	0.8	0.5	17	0.06
1464054	Rock	2.51	0.015	12.2	142.5	33.7	54	2.2	4.1	2.5	73	2.55	13.3	15.4	2.2	20	<0.1	0.9	0.7	8	0.03
1464055	Rock	1.96	0.040	10.7	203.4	19.1	80	2.5	12.4	19.0	1708	4.29	8.0	40.8	1.1	21	0.4	1.3	0.4	53	0.03
1464056	Rock	1.59	0.059	2.0	151.9	14.9	52	1.6	6.0	14.1	2366	2.30	14.9	62.7	0.8	20	1.3	5.4	0.2	9	0.04
1464057	Rock	1.79	0.162	1.5	154.9	302.3	69	4.8	4.3	9.9	1591	2.91	10.3	150.2	1.3	44	0.8	1.5	2.9	8	0.03
1464058	Rock	2.03	0.018	0.8	130.3	28.1	107	0.7	16.3	21.8	2229	4.36	2.6	16.0	0.8	34	1.7	0.9	0.3	95	2.48
1464059	Rock	1.87	0.013	1.1	60.1	12.8	61	0.5	15.0	15.1	1173	3.24	1.3	13.9	1.4	46	0.6	1.3	0.1	49	3.56
1464060	Rock	1.77	0.009	0.9	49.1	9.3	58	0.4	17.0	14.8	1172	3.25	1.9	11.5	1.4	42	0.6	1.4	<0.1	53	3.38
1464061	Rock	1.99	0.034	0.9	63.5	75.9	70	1.0	5.9	8.6	833	2.40	0.7	34.0	2.0	27	1.2	0.4	0.9	32	2.07
1464062	Rock	2.06	0.025	4.2	42.9	281.7	65	1.8	1.8	3.5	349	1.28	3.0	23.4	1.2	39	1.4	1.4	2.8	9	1.10
1464063	Rock	2.07	0.011	0.5	19.2	50.8	38	0.3	2.0	4.0	290	1.31	1.4	11.1	1.1	35	0.2	0.3	0.4	9	0.59
1464064	Rock	1.95	0.009	0.7	10.7	21.8	28	0.2	1.8	3.1	267	1.29	0.7	8.4	1.2	22	0.1	0.2	0.1	9	0.58
1464065	Rock	2.03	0.050	8.8	70.5	60.5	50	1.2	2.2	6.1	618	2.65	3.1	52.3	2.1	23	0.4	0.4	0.4	13	1.21
1464066	Rock	1.86	0.058	4.1	77.6	63.1	49	1.4	1.8	5.4	431	2.22	2.9	59.5	2.3	22	0.8	0.7	0.5	10	1.07
1464067	Rock	2.31	0.045	2.9	113.4	75.5	52	1.2	1.7	4.8	403	2.10	6.0	41.7	2.0	39	0.7	2.3	0.8	10	1.38
1464068	Rock	2.09	0.017	0.6	28.0	34.6	45	0.4	2.2	6.2	552	2.16	1.2	19.7	1.9	40	0.4	0.1	0.3	12	1.74
1464069	Rock	1.96	0.013	1.1	24.8	31.3	47	0.5	3.2	6.2	654	2.19	0.7	12.6	2.1	54	0.4	<0.1	0.6	22	2.42
1464070	Rock Pulp	0.12	0.870	4.3	31.0	5.1	50	0.3	24.6	8.9	401	2.54	6.5	573.0	0.9	41	0.1	0.8	0.1	62	0.86
1464071	Rock	2.06	0.005	0.9	21.8	60.1	64	0.4	13.3	9.7	920	2.73	<0.5	5.6	1.6	87	0.4	0.1	0.6	57	2.95
1464072	Rock	2.14	<0.005	0.7	21.9	55.9	69	0.2	13.1	18.2	1262	3.90	<0.5	4.6	0.5	187	0.2	0.2	0.5	84	4.00
1464073	Rock	2.09	<0.005	0.6	39.2	20.8	69	<0.1	13.2	22.6	1095	4.52	1.4	1.1	0.5	273	0.3	0.4	0.2	104	4.07
1464074	Rock	2.18	0.010	0.6	67.3	27.7	64	0.5	12.6	23.4	1099	4.54	2.7	9.7	0.4	270	0.3	0.3	0.3	101	3.92
1464075	Rock	2.12	0.029	0.6	68.5	14.1	64	0.9	8.1	20.0	1176	4.41	4.5	28.4	0.4	158	0.2	0.5	0.1	94	3.54
1464076	Rock	2.09	0.045	0.8	60.0	648.6	82	4.5	4.9	12.0	779	2.95	2.5	38.2	0.9	93	1.1	0.5	7.1	29	2.20
1464077	Rock	1.88	0.009	0.7	86.2	29.7	45	0.7	1.2	3.2	621	2.05	2.9	9.0	2.1	40	0.3	0.2	0.2	8	1.58
1464078	Rock	2.04	0.005	0.6	41.6	37.1	42	0.5	0.9	2.5	491	1.70	2.1	5.3	2.1	32	0.2	0.1	0.5	6	1.06
1464079	Rock	1.99	0.009	2.0	71.8	23.7	55	0.7	1.3	4.1	563	2.00	3.5	8.2	2.5	41	0.6	0.4	0.2	7	1.18
1464080	Rock Pulp	0.13	<0.005	2.1	22.5	2.1	40	0.2	20.6	9.5	364	2.22	4.3	0.7	0.8	37	0.1	0.3	<0.1	54	0.74
1464081	Rock	1.92	0.007	0.7	76.1	25.0	31	0.5	1.0	3.0	316	1.36	2.4	6.3	1.6	53	0.2	<0.1	0.1	6	0.68



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1464052	Rock	0.029	15	8	0.02	423	<0.001	<20	0.23	0.006	0.30	0.4	0.08	6.3	<0.1	0.31	<1	0.8	1.0
1464053	Rock	0.071	10	4	0.02	235	0.002	<20	0.20	0.009	0.74	0.5	0.09	9.5	<0.1	1.23	2	2.8	1.9
1464054	Rock	0.016	12	4	0.01	592	<0.001	<20	0.16	0.003	0.31	0.9	0.05	6.5	<0.1	0.46	<1	2.4	1.8
1464055	Rock	0.047	6	10	0.25	277	0.008	<20	0.60	0.007	0.46	0.6	0.11	23.8	0.2	0.32	3	2.0	1.6
1464056	Rock	0.026	3	4	0.02	94	<0.001	<20	0.31	0.002	0.14	0.5	0.07	8.7	<0.1	<0.05	<1	0.9	0.9
1464057	Rock	0.029	7	2	0.02	1371	<0.001	<20	0.28	0.006	0.19	0.3	0.13	11.1	<0.1	0.19	<1	2.1	2.1
1464058	Rock	0.025	7	14	0.57	496	0.021	<20	0.75	0.021	0.45	0.4	0.04	22.3	0.1	0.17	3	1.1	0.5
1464059	Rock	0.021	7	19	0.77	101	0.008	<20	0.50	0.029	0.30	0.4	0.04	16.3	<0.1	0.10	2	1.3	0.4
1464060	Rock	0.022	7	22	0.77	76	0.009	<20	0.53	0.025	0.32	0.2	0.03	17.5	<0.1	0.08	2	<0.5	0.2
1464061	Rock	0.026	10	5	0.23	110	0.004	<20	0.30	0.024	0.16	0.4	0.05	10.5	<0.1	0.10	1	<0.5	0.5
1464062	Rock	0.014	5	3	0.09	825	<0.001	<20	0.19	0.024	0.13	0.9	0.05	3.9	<0.1	0.12	<1	0.7	0.5
1464063	Rock	0.014	4	3	0.03	483	<0.001	<20	0.19	0.024	0.14	0.5	0.03	4.0	<0.1	0.14	<1	0.8	<0.2
1464064	Rock	0.021	2	3	0.03	192	<0.001	<20	0.22	0.025	0.16	0.5	0.02	3.4	<0.1	0.11	<1	0.7	<0.2
1464065	Rock	0.024	6	3	0.04	190	<0.001	<20	0.18	0.017	0.13	0.5	0.04	6.1	<0.1	0.52	<1	<0.5	1.0
1464066	Rock	0.024	9	3	0.04	40	<0.001	<20	0.23	0.020	0.16	0.4	0.04	6.1	<0.1	0.43	<1	1.6	0.9
1464067	Rock	0.026	7	4	0.15	444	<0.001	<20	0.27	0.025	0.19	0.5	0.04	5.6	<0.1	0.50	<1	2.2	0.6
1464068	Rock	0.025	6	3	0.40	422	0.001	<20	0.27	0.028	0.16	0.3	0.05	6.5	<0.1	0.40	<1	2.6	0.4
1464069	Rock	0.020	9	4	0.60	47	0.003	<20	0.23	0.029	0.14	0.5	0.05	8.2	<0.1	0.26	<1	2.5	0.2
1464070	Rock Pulp	0.055	5	33	0.75	95	0.136	<20	1.56	0.090	0.14	9.6	0.05	5.2	<0.1	<0.05	5	0.6	<0.2
1464071	Rock	0.027	8	29	1.03	214	0.009	<20	0.42	0.027	0.29	1.0	0.03	14.5	<0.1	0.21	2	1.0	<0.2
1464072	Rock	0.031	4	16	1.42	66	0.007	<20	0.58	0.032	0.40	0.5	0.02	22.0	<0.1	0.20	2	<0.5	<0.2
1464073	Rock	0.028	4	10	2.07	220	0.012	<20	0.65	0.025	0.34	0.2	0.01	23.5	<0.1	0.09	3	<0.5	<0.2
1464074	Rock	0.037	4	9	2.00	816	0.007	<20	0.64	0.026	0.36	0.3	0.04	24.5	<0.1	0.32	2	<0.5	0.3
1464075	Rock	0.041	4	8	1.49	198	0.023	<20	0.50	0.022	0.39	0.8	0.07	20.9	0.1	1.13	2	<0.5	0.6
1464076	Rock	0.027	3	4	0.78	189	0.003	<20	0.24	0.022	0.17	1.1	0.09	11.2	<0.1	1.18	1	2.0	1.2
1464077	Rock	0.025	5	3	0.50	68	0.002	<20	0.16	0.035	0.12	1.4	0.04	6.1	<0.1	0.46	<1	<0.5	0.4
1464078	Rock	0.022	5	4	0.34	46	0.002	<20	0.18	0.039	0.13	1.1	0.03	5.8	<0.1	0.30	<1	<0.5	0.2
1464079	Rock	0.026	6	3	0.39	58	<0.001	<20	0.13	0.022	0.11	2.3	0.05	5.4	<0.1	0.85	<1	<0.5	0.4
1464080	Rock Pulp	0.050	4	27	0.73	86	0.111	<20	1.44	0.075	0.13	11.3	<0.01	4.4	<0.1	<0.05	4	<0.5	<0.2
1464081	Rock	0.017	5	4	0.22	503	<0.001	<20	0.18	0.039	0.14	1.1	0.03	3.6	<0.1	0.52	<1	<0.5	0.3



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 3 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
1464082	Rock	1.81	<0.005	0.6	16.0	25.4	15	0.1	1.2	1.8	263	0.90	1.3	1.1	0.7	60	0.1	<0.1	<0.1	4	0.75
1464083	Rock	2.17	<0.005	1.3	37.3	16.5	48	0.2	1.4	3.8	482	1.78	1.3	4.2	2.1	47	0.1	<0.1	0.2	9	0.97
1464084	Rock	1.95	<0.005	0.8	39.9	7.7	50	<0.1	1.3	3.6	573	1.86	0.7	<0.5	2.6	38	<0.1	<0.1	<0.1	9	1.14
1464085	Rock	1.94	<0.005	0.9	24.8	13.2	49	<0.1	1.5	3.9	486	1.82	0.7	0.6	2.8	45	<0.1	<0.1	<0.1	14	0.87
1464086	Rock	1.80	0.008	0.7	62.0	16.0	38	0.3	1.7	3.8	369	1.55	2.2	6.1	2.1	49	<0.1	<0.1	0.1	7	0.75
1464087	Rock	2.09	0.008	1.0	62.7	14.8	44	0.2	1.6	4.2	507	2.10	1.6	3.3	2.5	37	<0.1	0.1	0.1	9	0.92
1464088	Rock	1.72	0.008	1.1	44.9	31.5	48	0.2	1.5	6.0	526	2.34	2.8	5.6	2.8	42	0.1	<0.1	0.1	8	0.99
1464089	Rock	1.81	<0.005	0.9	38.2	15.4	41	<0.1	1.1	3.5	419	1.83	0.8	<0.5	2.2	37	<0.1	<0.1	<0.1	8	0.90
1464090	Rock	2.00	<0.005	0.6	40.1	13.0	40	<0.1	1.5	3.4	426	1.89	0.9	1.0	2.4	39	<0.1	<0.1	<0.1	8	0.93
1464091	Rock	1.67	<0.005	0.9	44.6	19.3	43	<0.1	1.5	3.9	409	1.90	1.3	1.6	2.1	43	<0.1	<0.1	0.1	9	0.70
1464092	Rock	2.17	<0.005	0.9	42.3	12.7	50	<0.1	1.3	4.7	555	2.32	0.7	1.0	2.2	46	<0.1	<0.1	0.1	10	1.17
1464093	Rock	1.90	<0.005	0.9	39.6	7.8	41	<0.1	1.1	3.7	623	2.18	0.7	1.8	1.9	52	0.2	<0.1	<0.1	12	1.98
1464094	Rock	1.99	0.027	3.7	128.6	1436.6	561	6.8	5.1	7.4	743	2.37	5.4	21.8	0.9	79	28.3	0.5	12.2	15	2.27
1464095	Rock	2.11	0.029	9.1	135.8	256.1	116	1.9	8.1	8.5	829	2.79	6.0	27.1	0.5	112	4.0	0.3	2.6	21	3.08
1464096	Rock	1.84	<0.005	4.1	24.4	15.8	37	0.1	8.8	8.8	639	2.14	11.9	2.1	2.2	279	0.3	<0.1	0.3	11	4.38
1464097	Rock	0.84	<0.005	0.8	16.7	11.9	38	<0.1	9.2	7.7	841	2.85	3.7	1.1	2.9	321	0.2	<0.1	0.2	22	5.96
1464098	Rock	1.09	<0.005	1.1	8.1	4.4	20	0.1	1.7	2.7	274	1.46	1.4	0.8	4.8	130	<0.1	<0.1	0.5	4	1.32
1464099	Rock	2.37	<0.005	0.8	3.2	5.1	27	<0.1	1.5	2.7	339	1.65	1.1	1.1	5.7	137	<0.1	<0.1	0.2	8	1.42
1464100	Rock Pulp	0.12	2.212	66.8	2156.7	1361.9	3638	25.6	180.3	19.5	605	5.20	1200.3	734.7	2.4	80	17.8	13.1	9.2	56	1.45
1464101	Rock	1.90	<0.005	0.7	5.7	5.4	27	<0.1	2.0	4.3	357	1.85	1.4	<0.5	4.4	132	<0.1	<0.1	0.1	9	1.68
1464102	Rock	1.98	<0.005	0.7	9.2	4.7	34	<0.1	8.7	7.0	503	2.47	2.7	0.5	4.1	164	<0.1	<0.1	0.1	17	2.95
1464103	Rock	2.04	<0.005	0.9	12.5	3.8	32	<0.1	12.9	9.2	416	2.79	2.1	<0.5	6.2	124	<0.1	<0.1	0.2	21	1.90
1464104	Rock	1.87	<0.005	0.7	18.6	5.2	41	<0.1	14.4	9.3	483	2.80	2.4	<0.5	6.7	210	0.1	<0.1	0.2	20	3.30
1464105	Rock	1.66	<0.005	0.7	12.2	5.0	32	<0.1	14.6	9.2	474	2.51	2.6	0.9	6.3	206	<0.1	<0.1	0.2	17	3.65
1464106	Rock	2.18	<0.005	1.1	16.1	9.6	36	<0.1	15.4	10.7	510	2.77	3.6	1.3	5.2	289	<0.1	<0.1	0.2	22	6.13
1464107	Rock	1.58	<0.005	1.3	24.7	39.1	47	0.1	18.3	11.3	578	2.81	5.6	0.9	8.3	451	0.2	<0.1	0.4	20	9.71
1464108	Rock	1.97	<0.005	2.7	32.1	23.5	31	<0.1	11.3	5.5	279	1.52	4.0	0.8	2.2	606	<0.1	<0.1	0.1	11	11.19
1464109	Rock	2.22	<0.005	1.5	30.4	45.5	108	0.1	18.7	12.4	678	3.07	16.1	<0.5	7.8	324	0.7	<0.1	0.3	30	6.45
1464110	Rock Pulp	0.12	0.829	4.0	31.4	5.2	50	0.2	24.2	8.9	405	2.47	6.6	434.1	0.9	41	0.2	0.8	0.1	60	0.84
1464111	Rock	1.87	<0.005	2.5	32.7	8.8	46	<0.1	17.7	9.8	428	2.44	5.2	<0.5	8.4	256	0.2	<0.1	0.2	23	5.48



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method Analyte Unit MDL	AQ200 P %	AQ200 La ppm	AQ200 Cr ppm	AQ200 Mg %	AQ200 Ba ppm	AQ200 Ti %	AQ200 B ppm	AQ200 Al %	AQ200 Na %	AQ200 K %	AQ200 W ppm	AQ200 Hg ppm	AQ200 Sc ppm	AQ200 Ti ppm	AQ200 S %	AQ200 Ga ppm	AQ200 Se ppm	AQ200 Te ppm	
																			0.001
1464082	Rock	0.009	1	4	0.19	879	<0.001	<20	0.16	0.037	0.12	0.9	0.02	1.5	<0.1	0.26	<1	<0.5	<0.2
1464083	Rock	0.027	8	4	0.30	325	<0.001	<20	0.22	0.038	0.17	0.8	0.03	4.9	<0.1	0.31	<1	<0.5	<0.2
1464084	Rock	0.027	10	5	0.39	247	0.002	<20	0.20	0.032	0.17	0.9	0.03	5.3	<0.1	0.11	<1	<0.5	<0.2
1464085	Rock	0.031	12	6	0.33	256	0.005	<20	0.22	0.042	0.16	0.8	0.01	4.3	<0.1	0.14	1	<0.5	<0.2
1464086	Rock	0.021	8	5	0.27	345	0.002	<20	0.18	0.036	0.14	1.3	0.03	3.5	<0.1	0.37	<1	<0.5	0.3
1464087	Rock	0.027	9	5	0.38	317	0.002	<20	0.19	0.040	0.14	1.5	0.03	4.8	<0.1	0.38	<1	<0.5	<0.2
1464088	Rock	0.035	8	5	0.36	429	0.001	<20	0.24	0.037	0.16	0.5	0.08	5.6	<0.1	0.52	<1	<0.5	0.2
1464089	Rock	0.023	7	5	0.35	155	0.001	<20	0.18	0.041	0.12	0.5	0.03	4.5	<0.1	0.14	<1	<0.5	<0.2
1464090	Rock	0.025	7	5	0.35	161	0.002	<20	0.19	0.042	0.13	0.5	0.02	5.0	<0.1	0.13	<1	<0.5	<0.2
1464091	Rock	0.024	5	5	0.32	532	0.001	<20	0.18	0.037	0.13	0.9	0.02	4.4	<0.1	0.20	<1	<0.5	<0.2
1464092	Rock	0.027	7	5	0.43	55	0.001	<20	0.21	0.047	0.14	0.5	0.02	5.7	<0.1	0.17	<1	<0.5	<0.2
1464093	Rock	0.021	4	5	0.64	249	0.001	<20	0.19	0.037	0.13	0.4	0.06	5.7	<0.1	0.12	<1	<0.5	<0.2
1464094	Rock	0.017	2	7	0.72	169	<0.001	<20	0.17	0.017	0.12	2.2	0.76	6.0	<0.1	1.25	<1	4.5	0.9
1464095	Rock	0.008	2	8	1.01	60	<0.001	<20	0.20	0.006	0.14	1.8	0.33	7.1	<0.1	1.42	<1	2.1	1.0
1464096	Rock	0.014	2	7	0.70	361	<0.001	<20	0.35	0.016	0.23	0.2	0.50	5.5	0.1	0.47	<1	<0.5	<0.2
1464097	Rock	0.024	4	10	1.39	528	0.001	<20	0.32	0.023	0.22	0.1	0.19	6.8	<0.1	0.23	<1	<0.5	<0.2
1464098	Rock	0.010	4	4	0.40	434	<0.001	<20	0.19	0.026	0.16	0.2	2.22	2.3	0.2	0.16	<1	<0.5	<0.2
1464099	Rock	0.014	5	5	0.50	327	0.003	<20	0.36	0.026	0.27	0.2	1.01	3.4	<0.1	0.09	1	<0.5	<0.2
1464100	Rock Pulp	0.064	10	44	0.84	141	0.089	<20	1.47	0.083	0.19	7.5	0.71	4.1	1.2	1.47	5	3.3	0.4
1464101	Rock	0.010	3	5	0.56	667	0.001	<20	0.28	0.029	0.18	0.2	0.30	4.2	<0.1	0.20	<1	<0.5	<0.2
1464102	Rock	0.016	5	8	0.92	560	0.001	<20	0.33	0.027	0.21	0.2	0.31	5.4	<0.1	0.25	1	<0.5	<0.2
1464103	Rock	0.016	9	14	0.83	469	0.015	<20	0.60	0.024	0.43	0.2	0.31	5.3	0.1	0.26	3	<0.5	<0.2
1464104	Rock	0.025	9	13	0.96	762	0.007	<20	0.53	0.024	0.36	0.1	0.50	6.0	<0.1	0.36	2	<0.5	<0.2
1464105	Rock	0.031	8	13	0.80	550	0.008	<20	0.56	0.020	0.39	0.2	0.53	4.9	0.1	0.20	2	<0.5	<0.2
1464106	Rock	0.033	9	13	0.85	384	0.003	<20	0.50	0.022	0.33	0.2	0.46	6.6	<0.1	0.33	2	<0.5	<0.2
1464107	Rock	0.033	15	14	0.79	218	0.002	<20	0.37	0.023	0.23	0.2	0.45	6.6	<0.1	0.66	2	<0.5	<0.2
1464108	Rock	0.045	5	7	0.43	331	<0.001	<20	0.23	0.024	0.12	0.8	0.60	5.2	<0.1	0.77	1	0.8	<0.2
1464109	Rock	0.046	13	14	0.95	184	0.002	<20	0.43	0.025	0.22	0.3	1.15	9.4	0.1	0.43	2	<0.5	<0.2
1464110	Rock Pulp	0.054	5	31	0.73	96	0.126	<20	1.56	0.083	0.13	10.3	0.06	5.3	<0.1	<0.05	5	<0.5	<0.2
1464111	Rock	0.035	14	23	0.89	263	0.037	<20	0.73	0.024	0.51	0.7	0.54	5.9	0.1	0.42	4	0.8	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 4 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method	Analyte	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
Unit		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
MDL		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1464112	Rock	1.57	<0.005	0.8	22.4	6.5	59	<0.1	19.4	12.8	504	3.21	3.6	<0.5	9.8	123	<0.1	<0.1	0.1	27	1.33
1464113	Rock	1.61	<0.005	1.1	26.7	13.7	75	<0.1	20.1	11.9	516	2.85	5.5	0.8	10.4	169	<0.1	<0.1	0.2	24	3.51
1464114	Rock	2.04	<0.005	1.1	27.7	8.4	65	<0.1	21.3	10.4	474	2.99	1.1	<0.5	8.4	126	<0.1	<0.1	0.2	29	2.13
1464115	Rock	1.84	<0.005	1.2	66.0	64.2	196	0.1	16.5	10.4	539	2.80	2.1	<0.5	7.1	144	0.8	<0.1	0.2	16	2.50
1464116	Rock	2.40	<0.005	0.9	13.8	12.6	59	<0.1	13.3	11.4	941	3.10	1.3	<0.5	6.9	232	0.2	<0.1	0.3	42	5.23
1464117	Rock	1.81	<0.005	1.0	22.3	10.9	58	<0.1	18.3	11.5	737	3.08	0.9	<0.5	10.4	221	<0.1	<0.1	0.4	32	3.25
1464118	Rock	1.88	<0.005	1.4	11.5	9.5	50	<0.1	9.8	7.4	777	2.58	1.4	<0.5	4.9	215	0.2	<0.1	0.3	21	4.17
1464119	Rock	1.82	<0.005	0.6	20.0	5.4	74	<0.1	22.4	12.7	652	3.92	0.9	<0.5	12.2	81	0.1	<0.1	0.1	17	1.38
1464120	Rock Pulp	0.12	<0.005	2.3	23.7	2.2	42	0.2	21.9	9.4	411	2.41	4.3	<0.5	0.9	40	0.2	0.2	<0.1	59	0.85
1464121	Rock	2.17	<0.005	1.6	30.1	5.2	83	<0.1	18.0	11.8	673	3.44	0.7	<0.5	10.5	124	0.1	<0.1	0.1	31	1.43
1464122	Rock	1.80	<0.005	1.1	26.2	4.5	72	<0.1	21.3	13.0	640	3.52	0.7	<0.5	10.8	117	<0.1	<0.1	0.2	36	1.64
1464123	Rock	2.30	<0.005	0.9	17.4	3.3	59	<0.1	16.4	9.5	506	2.76	1.0	<0.5	9.2	91	<0.1	<0.1	<0.1	23	1.05
1464124	Rock	2.14	<0.005	0.9	22.9	12.8	70	<0.1	17.2	12.1	614	3.51	0.9	<0.5	9.9	69	<0.1	<0.1	0.2	40	0.95
1464125	Rock	2.11	<0.005	0.9	7.8	3.9	48	<0.1	10.5	7.0	494	2.29	0.6	<0.5	4.9	140	<0.1	<0.1	<0.1	22	1.44
1464126	Rock	1.74	<0.005	0.9	21.6	3.8	50	<0.1	12.8	10.5	503	2.76	0.6	<0.5	7.4	150	<0.1	<0.1	0.1	36	1.32
1464127	Rock	2.30	<0.005	1.0	26.0	3.1	54	<0.1	16.6	10.8	517	3.23	<0.5	<0.5	8.4	94	<0.1	<0.1	<0.1	41	0.81
1464128	Rock	2.24	<0.005	1.1	20.2	4.2	47	<0.1	21.0	11.1	484	2.87	0.5	<0.5	9.9	72	<0.1	<0.1	0.1	39	1.00
1464129	Rock	1.94	<0.005	0.7	13.1	2.8	45	<0.1	15.3	9.4	421	2.60	0.7	0.9	7.7	87	<0.1	<0.1	<0.1	44	1.03
1464130	Rock	2.10	<0.005	0.9	12.2	2.4	44	<0.1	16.0	8.7	414	2.57	<0.5	<0.5	7.5	83	<0.1	<0.1	<0.1	43	0.99
1464131	Rock	2.10	<0.005	0.9	12.3	3.2	50	<0.1	6.8	6.6	324	2.09	0.5	<0.5	5.7	172	<0.1	<0.1	0.1	36	0.91



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **Comstock Metals Ltd.**
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI16000440.1

Method	Analyte	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1464112	Rock	0.027	18	27	1.02	317	0.033	<20	0.78	0.026	0.56	0.3	0.17	6.5	0.1	0.32	4	<0.5	<0.2	
1464113	Rock	0.031	24	19	0.90	249	0.025	<20	0.69	0.026	0.44	0.3	0.35	5.4	0.2	0.27	4	<0.5	<0.2	
1464114	Rock	0.043	18	25	0.93	341	0.040	<20	0.76	0.031	0.51	0.3	0.16	6.2	0.1	0.24	4	<0.5	<0.2	
1464115	Rock	0.019	10	15	1.12	265	0.005	<20	0.49	0.027	0.32	0.2	0.55	5.3	<0.1	0.29	2	<0.5	<0.2	
1464116	Rock	0.029	16	25	1.20	509	0.026	<20	0.81	0.026	0.57	0.2	0.29	9.6	0.1	0.17	3	<0.5	<0.2	
1464117	Rock	0.028	23	24	1.02	569	0.028	<20	0.75	0.035	0.54	0.4	0.19	8.4	0.1	0.47	4	0.8	<0.2	
1464118	Rock	0.028	10	15	1.08	747	0.014	<20	0.59	0.028	0.40	0.3	0.06	5.5	<0.1	0.15	2	<0.5	<0.2	
1464119	Rock	0.029	21	14	1.19	127	0.008	<20	0.65	0.022	0.40	<0.1	0.09	6.0	<0.1	0.15	3	<0.5	<0.2	
1464120	Rock Pulp	0.058	4	29	0.79	90	0.127	<20	1.60	0.081	0.13	11.5	0.01	5.3	<0.1	<0.05	5	<0.5	<0.2	
1464121	Rock	0.066	21	34	1.12	358	0.064	<20	1.03	0.039	0.74	0.4	0.11	7.4	0.2	0.27	5	<0.5	<0.2	
1464122	Rock	0.044	18	28	1.19	336	0.070	<20	1.16	0.028	0.85	0.3	0.06	6.9	0.2	0.24	5	<0.5	<0.2	
1464123	Rock	0.028	14	21	0.89	334	0.060	<20	0.88	0.030	0.69	0.5	0.05	4.6	0.2	0.24	4	<0.5	<0.2	
1464124	Rock	0.036	16	21	1.08	321	0.099	<20	1.19	0.036	0.97	0.6	0.04	7.6	0.3	0.46	6	0.5	<0.2	
1464125	Rock	0.021	7	13	0.81	441	0.035	<20	0.64	0.035	0.47	0.6	0.03	4.7	0.1	0.11	3	<0.5	<0.2	
1464126	Rock	0.044	13	20	0.94	332	0.066	<20	0.91	0.041	0.70	1.2	0.07	8.1	0.1	0.29	4	0.5	<0.2	
1464127	Rock	0.047	16	23	1.00	405	0.087	<20	1.11	0.032	0.83	0.6	0.03	7.4	0.2	0.22	5	<0.5	<0.2	
1464128	Rock	0.033	20	34	1.10	412	0.108	<20	1.18	0.047	0.90	0.9	0.04	6.3	0.2	0.22	6	<0.5	<0.2	
1464129	Rock	0.032	14	32	1.10	482	0.085	<20	1.10	0.058	0.79	0.9	0.03	7.4	0.2	0.15	6	<0.5	<0.2	
1464130	Rock	0.033	14	30	1.13	451	0.087	<20	1.06	0.047	0.78	0.7	0.03	7.5	0.1	0.14	6	<0.5	<0.2	
1464131	Rock	0.042	9	18	0.74	558	0.083	<20	0.94	0.047	0.68	0.6	0.03	4.8	0.1	0.11	5	<0.5	<0.2	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 1 of 2 Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000440.1

Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
Pulp Duplicates																					
REP 1464060	QC	0.010																			
1464066	Rock	1.86	0.058	4.1	77.6	63.1	49	1.4	1.8	5.4	431	2.22	2.9	59.5	2.3	22	0.8	0.7	0.5	10	1.07
REP 1464066	QC	4.3		78.3	62.5	49	1.4	1.7	5.4	435	2.26	3.1	54.8	2.3	22	0.7	0.8	0.5	10	1.08	
1464073	Rock	2.09	<0.005	0.6	39.2	20.8	69	<0.1	13.2	22.6	1095	4.52	1.4	1.1	0.5	273	0.3	0.4	0.2	104	4.07
REP 1464073	QC	<0.005																			
1464095	Rock	2.11	0.029	9.1	135.8	256.1	116	1.9	8.1	8.5	829	2.79	6.0	27.1	0.5	112	4.0	0.3	2.6	21	3.08
REP 1464095	QC	0.031																			
1464100	Rock Pulp	0.12	2.212	66.8	2156.7	1361.9	3638	25.6	180.3	19.5	605	5.20	1200.3	734.7	2.4	80	17.8	13.1	9.2	56	1.45
REP 1464100	QC	64.4		2121.3	1351.9	3577	24.7	176.8	18.8	597	5.12	1179.1	1243.7	2.4	80	19.2	13.2	9.3	55	1.42	
1464127	Rock	2.30	<0.005	1.0	26.0	3.1	54	<0.1	16.6	10.8	517	3.23	<0.5	<0.5	8.4	94	<0.1	<0.1	<0.1	41	0.81
REP 1464127	QC	1.0		24.7	3.2	59	<0.1	17.6	11.0	535	3.34	0.9	<0.5	8.4	94	<0.1	<0.1	<0.1	42	0.84	
Core Reject Duplicates																					
1464060	Rock	1.77	0.009	0.9	49.1	9.3	58	0.4	17.0	14.8	1172	3.25	1.9	11.5	1.4	42	0.6	1.4	<0.1	53	3.38
DUP 1464060	QC	0.011		0.8	47.2	9.2	60	0.4	16.9	14.9	1157	3.27	1.5	10.0	1.3	42	0.6	1.3	<0.1	53	3.31
1464094	Rock	1.99	0.027	3.7	128.6	1436.6	561	6.8	5.1	7.4	743	2.37	5.4	21.8	0.9	79	28.3	0.5	12.2	15	2.27
DUP 1464094	QC	0.025		3.5	129.9	1405.5	570	6.6	5.3	7.5	753	2.41	5.4	23.2	0.9	80	27.0	0.6	12.3	15	2.25
1464128	Rock	2.24	<0.005	1.1	20.2	4.2	47	<0.1	21.0	11.1	484	2.87	0.5	<0.5	9.9	72	<0.1	<0.1	0.1	39	1.00
DUP 1464128	QC	<0.005		1.1	20.1	4.4	48	<0.1	21.2	11.3	481	2.91	<0.5	<0.5	10.0	73	<0.1	<0.1	0.1	39	1.01
Reference Materials																					
STD DS10	Standard	14.3		156.8	148.3	372	1.9	77.3	13.3	916	2.81	46.7	92.6	7.4	70	2.5	7.0	12.6	43	1.14	
STD DS10	Standard	13.5		147.4	150.0	350	1.7	71.1	12.3	835	2.62	42.9	66.6	6.8	63	2.1	6.9	12.6	41	1.00	
STD DS10	Standard	14.2		147.1	141.5	348	1.6	72.5	12.2	879	2.71	43.1	50.9	6.5	67	2.4	6.7	11.4	43	1.05	
STD OREAS45EA	Standard	1.4		697.0	12.3	31	0.3	389.0	50.0	436	21.00	10.1	52.2	8.5	4	<0.1	0.2	0.2	309	0.03	
STD OREAS45EA	Standard	1.4		671.3	11.7	28	0.2	375.5	48.2	391	20.72	9.8	43.0	8.0	3	<0.1	0.3	0.2	284	0.03	
STD OREAS45EA	Standard	1.3		644.0	12.9	27	0.2	362.7	47.2	381	20.34	9.3	47.5	9.4	4	<0.1	0.3	0.2	285	0.03	
STD OXC145	Standard	0.212																			
STD OXC145	Standard	0.204																			
STD OXH122	Standard	1.209																			



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 1 of 2 Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000440.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
Pulp Duplicates																			
REP 1464060	QC																		
1464066	Rock	0.024	9	3	0.04	40	<0.001	<20	0.23	0.020	0.16	0.4	0.04	6.1	<0.1	0.43	<1	1.6	0.9
REP 1464066	QC	0.024	8	3	0.04	38	<0.001	<20	0.23	0.020	0.16	0.4	0.07	6.4	<0.1	0.44	<1	1.4	1.0
1464073	Rock	0.028	4	10	2.07	220	0.012	<20	0.65	0.025	0.34	0.2	0.01	23.5	<0.1	0.09	3	<0.5	<0.2
REP 1464073	QC																		
1464095	Rock	0.008	2	8	1.01	60	<0.001	<20	0.20	0.006	0.14	1.8	0.33	7.1	<0.1	1.42	<1	2.1	1.0
REP 1464095	QC																		
1464100	Rock Pulp	0.064	10	44	0.84	141	0.089	<20	1.47	0.083	0.19	7.5	0.71	4.1	1.2	1.47	5	3.3	0.4
REP 1464100	QC	0.061	10	45	0.82	144	0.090	<20	1.46	0.082	0.19	8.1	0.67	4.3	1.3	1.44	6	3.1	0.5
1464127	Rock	0.047	16	23	1.00	405	0.087	<20	1.11	0.032	0.83	0.6	0.03	7.4	0.2	0.22	5	<0.5	<0.2
REP 1464127	QC	0.046	16	24	1.01	429	0.089	<20	1.14	0.034	0.87	0.6	0.03	7.5	0.2	0.23	5	<0.5	<0.2
Core Reject Duplicates																			
1464060	Rock	0.022	7	22	0.77	76	0.009	<20	0.53	0.025	0.32	0.2	0.03	17.5	<0.1	0.08	2	<0.5	0.2
DUP 1464060	QC	0.022	7	24	0.76	73	0.010	<20	0.57	0.031	0.34	0.2	0.03	17.7	<0.1	0.08	2	<0.5	0.3
1464094	Rock	0.017	2	7	0.72	169	<0.001	<20	0.17	0.017	0.12	2.2	0.76	6.0	<0.1	1.25	<1	4.5	0.9
DUP 1464094	QC	0.015	2	6	0.73	186	<0.001	<20	0.17	0.017	0.12	2.3	0.75	6.2	<0.1	1.23	<1	5.1	0.8
1464128	Rock	0.033	20	34	1.10	412	0.108	<20	1.18	0.047	0.90	0.9	0.04	6.3	0.2	0.22	6	<0.5	<0.2
DUP 1464128	QC	0.036	20	35	1.11	417	0.110	<20	1.18	0.048	0.91	1.0	0.04	6.4	0.2	0.23	6	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.077	17	55	0.80	418	0.078	<20	1.05	0.071	0.35	3.0	0.30	3.1	5.4	0.29	5	1.8	5.0
STD DS10	Standard	0.070	17	53	0.75	385	0.075	<20	0.97	0.066	0.32	2.8	0.27	2.7	4.8	0.27	4	2.1	4.9
STD DS10	Standard	0.073	17	54	0.77	392	0.077	<20	1.01	0.069	0.33	2.7	0.27	2.8	4.6	0.28	4	1.6	4.4
STD OREAS45EA	Standard	0.030	6	839	0.09	130	0.095	<20	3.17	0.021	0.05	<0.1	0.02	85.0	<0.1	<0.05	12	<0.5	<0.2
STD OREAS45EA	Standard	0.027	6	838	0.09	119	0.094	<20	3.14	0.021	0.05	<0.1	0.02	78.2	<0.1	<0.05	11	0.5	<0.2
STD OREAS45EA	Standard	0.026	6	795	0.08	131	0.092	<20	3.11	0.025	0.05	<0.1	<0.01	76.3	<0.1	<0.05	11	<0.5	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH122	Standard																		



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI16000440.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01	
STD OXH122	Standard		1.223																			
STD OXN117	Standard		7.711																			
STD OXN117	Standard		7.558																			
STD OXN117 Expected			7.679																			
STD OXC145 Expected			0.212																			
STD OXH122 Expected			1.247																			
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625	
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036	
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank		<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01	
Prep Wash																						
ROCK-WHI	Prep Blank		<0.005	0.7	5.3	1.6	30	<0.1	1.0	3.5	404	1.70	0.8	0.5	2.3	28	<0.1	<0.1	<0.1	22	0.64	
ROCK-WHI	Prep Blank		<0.005	0.6	3.8	1.3	28	<0.1	0.7	3.7	415	1.72	0.7	0.7	2.5	25	<0.1	<0.1	<0.1	22	0.57	



Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: Comstock Metals Ltd.
310 - 850 West Hastings St.
Vancouver British Columbia V6C 1E1 Canada

Project: QVV
Report Date: December 10, 2016

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI16000440.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200		
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
STD OXH122	Standard																			
STD OXN117	Standard																			
STD OXN117	Standard																			
STD OXN117 Expected																				
STD OXC145 Expected																				
STD OXH122 Expected																				
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01	
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07	
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	0.7	<0.2	
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2	
Prep Wash																				
ROCK-WHI	Prep Blank	0.038	5	2	0.38	68	0.089	<20	0.85	0.080	0.09	0.1	<0.01	2.4	<0.1	<0.05	4	<0.5	<0.2	
ROCK-WHI	Prep Blank	0.040	6	2	0.40	64	0.085	<20	0.81	0.064	0.07	0.1	0.01	2.5	<0.1	<0.05	4	<0.5	<0.2	