MAP NO.:	ASSESSMENT REPORT	X	DOCUMENT NO: 092795
	PROSPECTUS		MINING DISTRICT: Mayo
106 D 7	CONFIDENTIAL	X	TYPE OF WORK:Geology, Geochemistry,
	OPEN FILE		Geophysics, Diamond Drilling

REPORT FILED UNDER: NDU Resources Ltd./Billiton Metals Canada Inc.

DATE PERFORMED: July 89 **DATE FILED:** December 27, 1989

LOCATION: **LAT.:** 64° 24'N **AREA:** Wernecke Mountains

LONG.: 134° 40'W **VALUE $:** 55 182.31

CLAIM NAME & NO.:
BLENDE 1-15 YA 43524-538
BLENDE 16-56 YB 02529-569
BLENDE 57-66 YB 02700-709
BLENDE 67-122 YB 03051-106

WORK DONE BY: Archer, Cathro and Associates (1981) Ltd.

WORK DONE FOR: NDU Resources Ltd./Billiton Metals Canada Inc.

DATE TO GOOD STANDING:

REMARKS: #47 BLENDE Mineralization occurs in fractures as tabular breccia and stockwork zones within an up to 200 m wide composite faul system cutting Proterozoic dolomite. Ore minerals are galena, sphalerite, and pyrite with minor chalcopyrite and tetrahedrite. Best diamond drill assays come from Hole 88-2 which averaged 5.2% Pb, 2.8% Zn and 108.9 g/t Ag over 81.7 metres.

BLENDE PROPERTY
1989 FINAL REPORT

RECEIVED
DEC 27 1989
MINING RECORDER
MAYO, Y.T.
I.A. & N.D.

092795

FIGURE NO.		POCKET
	Text	A
	Appendix A	A
	Appendix B	A
	Appendix C	B
	Appendix D	C
1	Location Map	In Text
2	Claim Location	In Text
3	Regional Geological Setting	In Text
4	Geology and Mineralization	In Text
5	Geological and Geochemical Compilation	D
6	Geology	E
7	Stratigraphic Column	In Text
8	Geological Cross Section	In Text
9	Detailed Geology and Mineralization (West Sheet)	F
10	Detailed Geology and Mineralization (East Sheet)	F
11	Vertical Cross Section, DDH 88-1	In Text
12	Vertical Cross Section, DDH 88-2	In Text
13	Vertical Cross Section, DDH 88-3	In Text
14	Sample Locations	G
15	Lead Geochemistry	H
16	Zinc Geochemistry	I
17	Silver Geochemistry	J
18	Copper Geochemistry	K
19	Arsenic Geochemistry	K
20	Fraser Filtered VLF	L

092795

ARCHER, CATHRO
& ASSOCIATES (1981) LIMITED
CONSULTING GEOLOGICAL ENGINEERS

1016 - 510 WEST HASTINGS STREET
VANCOUVER, B. C. V6B 1L8
(604) 688-2568

RECEIVED
DEC 27 1989
MINING RECORDER
MAYO, Y.T.
I.A. & N.D.

BLENDE PROPERTY

1989 FINAL REPORT

WERNECKE MOUNTAINS, YUKON TERRITORY

Latitude 64°24'N; Longitude 134°40'W

NTS 106D/7

092795

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

D. Lister, B.A.Sc.

D. Eaton, B.A.,B.Sc.

December, 1989

BOX 4127, 3125 THIRD AVENUE, WHITEHORSE, Y.T. Y1A 3S9
(403) 667-4415

This report has been examined by the Geological Evaluation Unit under Section 53 (4) Yukon Quartz Mining Act and is allowed as representative work in the amount of $ 55,182.31 .

for Regional Manager, Exploration and Geological Services for Commissioner of Yukon Territory.

TABLE OF CONTENTS

	PAGE
SUMMARY AND RECOMMENDATIONS	1
INTRODUCTION	4
LOCATION, CLAIM STATUS, ACCESS AND INFRASTRUCTURE	6
GEOMORPHOLOGY	8
REGIONAL GEOLOGY	9
PROPERTY GEOLOGY	11
REGIONAL MINERALIZATION	15
PROPERTY MINERALIZATION	17
GEOCHEMISTRY	23
GEOPHYSICS	29
CONCLUSIONS AND DISCUSSION	30
REFERENCES	31

TABLES

1	Significant Drill Intersections, Blende Property	20
2	Summary of Major Soil Geochemical Anomalies on the Blende Grid	26

APPENDICES

A	Authors' Statements of Qualifications	In Text
B	List of Personnel	In Text
C	Certificates of Analysis	In Pocket
D	1988 Drill Logs	In Pocket

LIST OF FIGURES

NUMBER		LOCATION
1	Location Map	Following Page 6
2	Claim Location	Following Page 6
3	Regional Geological Setting	Following Page 9
4	Geology and Mineralization	Following Page 11
5	Geological and Geochemical Compilation	In Pocket
6	Geology	In Pocket
7	Stratigraphic Column	Following Page 11
8	Geological Cross Section	Following Page 11
9	Detailed Geology and Mineralization (West Sheet)	In Pocket
10	Detailed Geology and Mineralization (East Sheet)	In Pocket
11	Vertical Cross Section, DDH 88-1	Following Page 19
12	Vertical Cross Section, DDH 88-2	Following Page 19
13	Vertical Cross Section, DDH 88-3	Following Page 19
14	Sample Locations	In Pocket
15	Lead Geochemistry	In Pocket
16	Zinc Geochemistry	In Pocket
17	Silver Geochemistry	In Pocket
18	Copper Geochemistry	In Pocket
19	Arsenic Geochemistry	In Pocket
20	Fraser Filtered VLF	In Pocket

SUMMARY AND RECOMMENDATIONS

The Blende property is wholly owned by NDU Resources Ltd. (NDU) which entered into an option agreement with Billiton Metals Canada Inc. on October 5, 1989. The agreement permits Billiton to earn a 50% interest in the property by making exploration expenditures of $4,000,000 and cash payments of $300,000 to repay NDU for work conducted prior to 1989, all before December 31, 1991. If NDU elects not to participate in further work after the 50% earn-in, Billiton can earn up to 70% interest by spending a further $3,000,000 and paying NDU an additional $300,000 before December, 31, 1992.

The 122 claim property covers approximately 25 sq km in central Yukon and is located 67 km northeast of Elsa, which is 600 km by all-weather road from the seaport at Skagway, Alaska.

Mineralization occurs in fractures as tabular breccia and stockwork zones within an up to 200 m wide composite fault system cutting Proterozoic dolomite. The ore minerals are a metallurgically simple assemblage of galena, sphalerite and pyrite with minor chalcopyrite and tetrahedrite. The gangue is predominantly secondary dolomite and iron carbonate.

Geological mapping and prospecting have traced the faults and mineralization over a 6000 m strike length while geochemical surveys in the western and central part of the system have outlined a 3800 by 250 m area of strongly anomalous lead, zinc and silver response. In 1988, three holes were drilled in the western part of the system. All three returned long mineralized intercepts with the best assays coming from Hole 88-2 which averaged 5.2% Pb, 2.8% Zn and 108.9 g/t Ag across 81.7 m, including 19.8 m grading 12.3% Pb, 4.4% Zn and 284.8 g/t Ag. None of the holes tested the entire width of the system or the area of highest grade surface mineralization.

The Blende property has potential for a large tonnage of moderate grade mineralization that could be mined by low cost, open pit methods. The next phase of exploration will consist of approximately 3650 m of diamond drilling in widely spaced holes using a camp, bulldozer and diamond drill already on the property. A copy of the proposed budget for 1990 is on the following page.

Respectfully submitted,

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

D. Lister, B.A.Sc.

D. Eaton, B.A., B.Sc.

PROPOSED 1990 BUDGET
BLENDE PROJECT

The following assumes a budget of $1,000,000 for 1990. A seven-man field crew plus a bulldozer operator will be moved to the camp in late May and a four-man drill crew will be added about June 15. Drilling is expected to be completed in early September.

Diamond Drilling 3658 m (12,000 ft) BQ at $98/m ($30/ft) direct payments to the contractor	$ 360,000
Salaries Geologist for 8 months; camp manager for 4 months; cook, assistant core logger, two core splitters and bull cook for 3-1/2 months; 120 days senior supervision; expediting, accounting and secretarial	195,000
Helicopter 175 hrs Bell 206 (Jet Ranger) @ $680/hr, including fuel	119,000
Field Room and Board - 1300 mandays @ $60/day	78,000
Bulldozer 320 hrs D-7 @ $130/hr including fuel, for preparing drill sites and moving drill	42,000
Assaying	40,000
Field Truck Purchase of a small 4-wheel drive truck, plus cost of positioning with a Bell 204 or 205 helicopter	30,000
Travel and Freight	22,000
Drafting and Printing	8,000
Assessment Filing	7,000
Environmental - preliminary water analyses	4,000
Management Archer, Cathro - $45,000 Billiton - 50,000	95,000
TOTAL -	$1,000,000

INTRODUCTION

The Blende silver-lead-zinc property is owned 100% by NDU Resources Ltd. and was optioned to Billiton Metals Canada Inc. on October 5, 1989. Upon signing, Billiton paid NDU $100,000 as a partial reimbursement of the 1988 exploration costs on the property. Billiton will repay 1989 exploration costs on the property to December 31, 1989 (up to a maximum of $500,000) and has guaranteed an additional $1,000,000 in exploration expenditures before December 31, 1990. Billiton can earn a 50% interest in the property by spending a total of $4,000,000 before December 31, 1991 and paying an additional $200,000 to NDU to complete the reimbursement of the 1988 exploration costs. If NDU elects not to participate in further work after the 50% earn-in, Billiton can earn up to a 70% interest by paying NDU $300,000 and spending a further $3,000,000 before December 31, 1992.

The property was first staked as the Will 1-60 claims by Cyprus Anvil Mining Corporation in July, 1975 after lead-zinc mineralization was discovered while following up anomalous stream sediment samples. The claims were explored later that year with reconnaissance sampling, geological mapping and prospecting (Roberts and Dean, 1975). Although Cyprus Anvil recognized the deposit had considerable grade and tonnage potential, the claims were dropped when the company's focus shifted to stratiform shale-hosted mineralization.

Archer, Cathro & Associates (1981) Limited restaked the main area of interest as the Blende 1-15 claims in March, 1981 and that summer collected several rock samples during a brief examination to evaluate silver potential. In 1982, further rock and chip sampling was conducted along with some peripheral prospecting and an airphoto interpretation of linear structures. More systematic chip sampling and hand trenching were done during 1984 in a joint venture with Norvista Development Ltd. (Cathro and Carne, 1984).

In 1986, the claims were vended to NDU Resources Ltd. which explored by prospecting and three diamond drill holes totalling 718 m in 1988. Upon receipt of favourable drill results, the claim block was increased to 66 claims, a hand trench was dug, aerial photographs were flown and ore mineralogy was studied.

In 1989, NDU mobilized a ripper-equipped D-7F bulldozer and a Longyear 38 diamond drill to the property, constructed a 15 man camp, built 9 km of four-wheel drive roads, staked 56 additional claims, and conducted geological mapping, grid soil sampling and VLF-EM and magnetic surveys. The work was supervised by D. Eaton, with field management by D. Lister. Appendix A contains the Authors' Statements of Qualifications and Appendix B lists personnel who worked on the project.

LOCATION, CLAIM STATUS, ACCESS AND INFRASTRUCTURE

The Blende property is located in central Yukon at latitude 64°24'N and longitude 134°40'W on NTS map sheet 106D/7, as shown on Figure 1 on the following page. It consists of 122 claims registered with the Mayo Mining Recorder as listed below and shown on Figure 2 (following Figure 1).

Claim Name	Total	Record Numbers	Expiry Date*
Blende 1- 15	15	YA43524-YA43538	March 11, 1994
16- 56	41	YB02529-YB02569	March 11, 1994
57- 66	10	YB02700-YB02709	March 11, 1994
67-104	38	YB03051-YB03088	June 21, 1990
105-122	18	YB03089-YB03106	July 13, 1990
	122		

*does not include 1989 assessment credits

The claims lie 67 km northeast of the mining community of Elsa and are accessible by helicopter or a 70 km winter trail. The first 60 km of the land route follows the Wind River Trail, an established winter road that joins the government-maintained, all-weather road system at McQuesten Lake, some 20 km northeast of Elsa. The last 10 km were completed in the spring of 1989 when the bulldozer and drill were mobilized to the property.

In 1989, approximately 9 km of four-wheel drive roads were built from the camp to the main areas of interest on the property, as shown on Figure 2.

Total road distance from Blende to the seaport of Skagway, Alaska is about 729 km which is comparable with other lead-zinc deposits in the Yukon and Northern B.C. such as: Faro (536 km), Logan (592 km), Hundere (706 km), Tom-Jason (777 km), Howards Pass (978 km), and Cirque (1216 km to the nearest seaport at Prince Rupert, B.C.). An under-utilized hydroelectric dam, which formerly provided power to the United Keno Hill Mines Ltd. operation at Elsa is located near Mayo, some 110 km by road from the property.



★ Major lead + zinc deposit

▲ Lead + zinc ± silver deposit mentioned in text

--- Winter trail

Figure 1

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

LOCATION MAP

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

0 50 100 150 200 Km

0 50 100 150 Miles





Four wheel drive road

Winter trail

Figure 2

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

CLAIM LOCATION

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

SCALE 1 Inch= 1/2 Mile (1:31,680)

0 500 1000 1500 2000 2500 Metres

0 1500 3000 4500 6000 7500 Ft

The 1989 program was supported by a Bell 206B helicopter contracted from Trans North Air of Whitehorse. The machine was based at an expediting basecamp (Sadie Camp), 5 km north of Keno, and was shared with two other exploration programs, plus Geological Survey of Canada (GSC) and Department of Indian and Northern Development (DIAND) crews mapping in the area.

GEOMORPHOLOGY

The Blende property is centred on Mt. Williams, a prominent peak in the southern Wernecke Mountains which form the divide between the Yukon River watershed to the south and MacKenzie River drainages to the north. Local elevations range from 1130 to 1875 m above sea level.

The area has undergone Pleistocene to Recent alpine glaciation and cirques are common at elevations above 1370 m. Outcrop is most abundant on steep, north-facing cirque walls, along ridge tops and in actively eroding creek cuts. South-facing hillsides are normally blanketed by talus. Frost action on over-steepened slopes has caused numerous landslides, the largest of which covers a 30,000 sq m area near the head of Dean Creek.

Treeline is at about 1300 m and aside from sparse grass and lichen, most of the property is unvegetated. Soil development is poor and usually consists of "C" horizon decomposed bedrock mixed with poorly developed "B" horizon material.

REGIONAL GEOLOGY

The Blende area lies immediately north of a regional-scale thrust fault (Kathleen Lakes Fault Zone) and is underlain by Late to Middle Proterozoic, Beltian- and Windermere-equivalent marine sediments capped by Early Paleozoic Mackenzie Platform strata (Roots, in press).

The Middle Proterozoic shelf assemblage, known as the Wernecke Supergroup, was deposited during periodic extensional events outboard from an east-west trending continental margin that lay north of the present Wernecke Mountains. Mesozoic thrust and high angle faults displaced the Wernecke Supergroup sediments northward and upward so they are now exposed in an arc extending from the Yukon-Alaska border to the eastern Wernecke Mountains, as shown in Figure 3 on the following page.

The Wernecke Supergroup has been subdivided into the Fairchild Lake, Quartet, and Gillespie Lake Groups (Delaney, 1981). The Fairchild Lake Group is the oldest unit and consists of about 1000 m of deep water siltstone and mudstone. It is overlain by about 3000 m of Quartet Group, stagnant basin and shallow marine, interbedded quartzite and pelitic rocks. Both groups have been deformed locally and metamorphosed to slate and phyllite. The Gillespie Lake Group unconformably overlies the older groups and consists of a 1200 m thick sequence of interbedded clastic and carbonate sedimentary rocks that progressively transform from predominantly deep water mudstone to shallow water stromatolitic dolomite.

Extensional stresses following deposition of the Gillespie Lake Group created small local basins in which Late Proterozoic sedimentary rocks were deposited. In the Blende area, these strata include shale, dolomite, siltstone and minor sandstone that are stratigraphically equivalent to the Pinguicula Group which Eisbacher (1981) mapped about 40 km northeast of the property.



LEGEND

- Thrust fault
- Transcurrent fault
- Window of Middle Proterozoic Wernecke Supergroup
- ★ Major lead ± zinc ± silver occurrence

Figure 3

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

REGIONAL GEOLOGICAL SETTING

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

0 20 40 60 80 100 Km

Paleozoic limestone and dolomite unconformably overlie the Proterozoic units and cap several ridges in the area.

A 75 km long, east-west trending belt of dioritic to gabbroic sills and dykes is developed along the north side of the Kathleen Lakes Fault Zone. These intrusions are probably Late Proterozoic in age as they intrude Gillespie Lake Group and some Pinguicula Group strata but do not cut the Paleozoic platform carbonates.

The dominant structures are broad folds and south-dipping thrust faults which strike east-west and are related to the Late Mesozoic to Early Tertiary Laramide Orogeny. The folds generally plunge gently to the east and overprint at least one phase of earlier folding that affects the Proterozoic strata. Several generations of high angle faults have been recognized, ranging from Helikian age structures that cut only Wernecke Supergroup rocks to relatively recent structures that postdate the Laramide Orogeny thrust faults.

PROPERTY GEOLOGY

Figure 4 on the following page shows simplified property geology while Figure 5 in the pocket is a 1:10,000 scale compilation map illustrating property geology, mineralization and geochemical results. Figure 6, also in the pocket, is a 1:5,000 scale outcrop geology map covering the central part of the property. The maps are based on 1989 work conducted by Archer, Cathro geologists, supplemented with several traverses in the area by C. Roots of the GSC and his colleagues P. Mustard and J. Donaldson of Carleton University. Additional geological data was drawn from earlier Archer, Cathro reports, GSC publications and DIAND mapping, listed in the references.

Rocks on the Blende property have been tentatively subdivided into seven sedimentary units and one intrusive unit, as described below. Figures 7 and 8 (following Figure 4) are a simplified stratigraphic column and geological cross section, respectively.

Quartet Group

Only the top 200 m of the Quartet Group succession is seen on the Blende property. This unit, designated Q2, is a monotonous sequence of black slate, phyllite and argillite with minor interbedded quartzite. The Q2 rocks exhibit a pervasive micaceous cleavage which fractures to create long indurated splinters in talus. The upper contact of the unit has previously been considered transitional into Gillespie Lake Group sediments (Delaney, 1981); however, recent mapping suggests the Quartet Group is more deformed than succeeding units. No contacts were observed in the immediate vicinity of Blende but Roots (in press) has observed angular relationships between the two at locales 100 km west of the property.



LEGEND

PALEOZOIC

PC — light grey weathering dolomite and limestone

LATE (?) PROTEROZOIC

diorite and gabbro

LATE PROTEROZOIC
PINGUICULA GROUP

P3 — black shale with basal conglomerate

P2 — red weathering dolomite

P1 — argillite, shale and chert

MIDDLE PROTEROZOIC
GILLESPIE LAKE GROUP

G2 — orange weathering dolomite

G1 — interbedded shale and dolomite

QUARTET GROUP

Q2 — interbedded shales, phyllites, argillites and quartzites

geological contact (defined, inferred)

high angle fault (defined, inferred)

thrust fault (defined, inferred)

★ Pb–Zn occurrence

Figure 4

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

GEOLOGY AND MINERALIZATION

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:50,000

0 1 2 km



unconformity

dolomite, dolomitic sandstone and mudstone

shale and siltstone

domal and columnar stromatolites

fine 'budding' stromatolites

oolites

conglomerate

chert

mineralized breccia

diorite or gabbro

Figure 7

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

STRATIGRAPHIC COLUMN

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.



SECTION FACING WEST

LATE (?) PROTEROZOIC

diorite and gabbro

LATE PROTEROZOIC
PINGUICULA GROUP

P_2 red weathering dolomite

P_1 argillite, shale and chert

MIDDLE PROTEROZOIC
GILLESPIE LAKE GROUP

G_2 orange weathering dolomite

G_1 interbedded shale and dolomite

QUARTET GROUP

Q_2 interbedded shales, phyllites, argillites and quartzites

fault

geological contact

mineralized zone

Figure 8

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

GEOLOGICAL CROSS SECTION

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

0 100 200 300 m

To accompany report dated December, 1989

Gillespie Lake Group

The Gillespie Lake Group is subdivided into two units: a deep water clastic sequence; and, a shallow water predominately carbonate package. The lower unit (G1) is about 450 m thick and consists of repeated 1 to 5 m thick cycles containing maroon or green weathering mudstone and shale beds alternated with light orange weathering dolomitic sandstone horizons. The rocks have a striped appearance in outcrop and break to form flat, rhomb-shaped talus.

The upper unit (G2) is approximately 250 m thick and hosts the main zones of silver-lead-zinc mineralization on the Blende property. It mainly consists of thick bedded grey dolomite and dolomitic mudstone containing abundant domal and columnar stromatolite beds up to 4 m thick. Fine interbeds of sandstone, shale, mudstone and chert also occur throughout the section. A thin oolitic bed found in two separate locations near the middle of the section on the property and a thin green volcanic layer noted just above the G1-G2 contact in localities off the property may be useful marker horizons. G2 rocks generally weather buff-orange to brown and break into irregularly shaped boulders.

Pinguicula Group

Regionally, Roots (in press) observed that no single stratigraphic section of the Pinguicula Group is representative and did not further subdivide the unit. However, on the property, three distinct sequences were noted.

Unit P1 (formerly Unit G2b of Cathro and Carne, 1984) is a 50 m thick sequence of dark siliceous siltstone and fine sandstone with thin dolomitic mudstone interbeds. The unit discontinuously overlies G2 and was probably deposited in localized basins.

Unit P2 (formerly Unit G3 of Cathro and Carne, 1984) conformably overlies P1 or unconformably overlies G2. It is about 250 m thick and consists of red-brown weathering massive grey dolomite containing fine hair-like stromatolites with diagnostic small budding heads atop larger columns (Mustard et al., in press).

Unit P3 is a 300 m thick section of dark grey weathering interbedded shale and siltstone. A narrow conglomerate horizon containing boulder- to pebble-sized clasts of gabbro and shale occurs near the base of the unit.

Several features of the Pinguicula Group pelitic rocks distinguish them from similar Quartet Group strata, including greater colour variation and presence of thin carbonate interbeds in the younger group. Pinguicula Group rocks also tend to break into small chips rather than the splintery talus characteristic of the older unit (Roots, in press).

Paleozoic Carbonates

Approximately 150 m of light grey weathering carbonate strata (Pc) unconformably caps the darker coloured Proterozoic assemblage in the Blende area. The base of the Paleozoic unit is marked in some areas by a thin bedded dolomite sequence tentatively correlated to the Cambrian Taiga Formation (Norris, 1982). These rocks are occasionally brecciated and exhibit siderite replacement along laminae and in fractures. Most of the Paleozoic sequence is comprised of relatively massive, fine-grained dolomite with abundant open spaces that are occasionally filled with quartz. These rocks are believed to range from Cambrian to Devonian in age and are analogous to GSC units CDb or OSc elsewhere in the Wernecke Mountains.

Intrusive Rocks

Dioritic to gabbroic dykes and plugs intrude the Proterozoic sediments in the Blende area. They are dark green, medium grained and contain about equal amounts of felsic (plagioclase with minor quartz) and mafic (clinopyroxene with minor hornblende) minerals (Green, 1972). Most are red-brown on weathered surfaces, but some are light green and show remnant grain textures. The thicker intrusions form prominent cliffs while the thinner bodies normally do not outcrop. Bleached dedolomitization halos are often developed where the intrusions cut Gillespie Lake Group dolomites. These zones are 1 to 30 m wide and contain secondary calcite and talc with rare gem quality axinite.

REGIONAL MINERALIZATION

Numerous silver-lead-zinc deposits occur north and northeast of Mayo. The most significant are described below and their locations are shown on Figure 3.

The best known deposits are the veins in the Keno Hill camp, which have produced 6,784,000 kg of silver since 1921. The veins contain galena, sphalerite and pyrite with siderite and quartz, plus a variety of primary and secondary silver minerals, the most important of which is freibergite. They cut quartzites and schists of the Keno Hill Quartzite, which was previously mapped as Cretaceous but is now assigned a Mississippian age. This same unit also hosts the Marg polymetallic massive sulphide deposit, 40 km northeast of Keno Hill. The Marg deposit occurs in metamorphosed pelitic and volcanic rocks and contains indicated and inferred reserves totalling 3.4 million tonnes grading 1.8% Cu, 2.7% Pb, 5.0% Zn, 65.1 g/t Ag and 1.2 g/t Au.

Numerous lead-zinc prospects with varying amounts of silver occur on the north side of the Kathleen Lakes Fault Zone. The Pinguicula Group and Paleozoic carbonates host stratabound mineralization while the Gillespie Lake Group contains stratiform and structurally controlled deposits.

Hart River is the best documented stratiform occurrence and reportedly contains proven and probable reserves of 1.1 million tonnes grading 1.4% Cu, 0.9% Pb, 3.6% Zn, 49.7 g/t Ag and 1.4 g/t Au. The mineralization consists of finely layered pyrite, pyrrhotite, sphalerite, and galena in a 19 m thick lens at a facies boundary between Gillespie Lake Group dolomite and shale. The deposit is unconformably overlain by Pinguicula Group strata and is cut by numerous mafic sills and dykes. Other stratiform occurrences within the Gillespie Lake Group (Cord and Jolly) have received relatively little exploration and contain pyrite, sphalerite and minor galena in horizons up to

2 m thick in dolomitic shale sequences within Unit G2. Lead isotope ratios for galena specimens from Hart River and Cord have returned model ages ranging from 1.2 to 1.5 bya (Godwin et al, 1988).

Structurally controlled deposits (which include Blende and the Vera and and Val properties owned by International Prism Exploration Ltd.) consist of tabular, steeply-dipping vein, stockwork and breccia zones cutting upper Gillespie Lake Group dolomite (Unit G2). Detailed descriptions of Blende appear in the following section. The Vera deposit has estimated reserves of 1.4 million tonnes averaging about 3.7% Pb + Zn with 306 g/t Ag, while Val contains indicated reserves of 60,000 tonnes grading 1030 g/t Ag. Lead isotope studies and structural and stratigraphic relationships indicate that Blende is Helikian age but the Prism deposits are much younger, probably Cretaceous.

Most mineralization in the Pinguicula Group and younger carbonate rocks occurs as Mississippi-valley type fracture filling and manto-type replacement bodies. Some of these occurrences are relatively high grade (greater than 10% Pb + Zn) but they are small (less than one million tonnes).

PROPERTY MINERALIZATION

Most silver-lead-zinc mineralization discovered to date on the Blende property occurs where an Helikian age fault complex cuts Unit G2, the 250 m thick dolomite sequence that comprises the upper part of the Gillespie Lake Group. The fault complex is up to 200 m wide and is composed of a strong footwall break (Footwall Fault) plus several weaker structures in the hanging wall. All of the faults strike between 105 and 110°, dip to the south at about 65° and exhibit a few metres of reverse dip slip offset. The mineralization has been intermittently traced in outcrop and float over a 6000 m strike length, with the largest gap occurring where the complex is capped by the younger Pinguicula Group shales. At the extreme west end, the faults cut into the underlying Unit G1 shales and appear to rapidly horsetail and pinch out. To the east they are cut off at surface by a thrust fault.

The mineralization is fracture controlled with the highest concentration occurring within 1 to 20 m wide stockwork and breccia zones developed along the main faults. It consists of medium-grained galena, sphalerite and pyrite, with minor chalcopyrite and tetrahedrite in a gangue of secondary dolomite, siderite and minor quartz. Sphalerite is generally pale grey or honey coloured, which makes the zinc grade difficult to visually estimate. Aside from minor bleaching, the mineralized rocks appear to be unaltered; however, unmineralized rocks in the footwall of the complex contain a high density of quartz-siderite veinlets which give the rock a dark brown colour and make it resistant to weathering. Well mineralized material weathers recessively and tends to break into smaller than fist-sized fragments that are usually covered by coarser unmineralized talus. The best exposures occur on steep slopes and ridge crests near the west end of the complex.

Samples from stockwork and breccia zones typically assay between 8 and 15% Pb+Zn while the surrounding weakly fractured wallrocks normally grade between 1 and 4% Pb+Zn. Silver to lead ratios range from approximately 0.2:1 to 3:1 and average about 0.7:1. Preliminary work suggests there is some metal zoning with increasing copper values and silver to lead ratios toward the base of Unit G2; however, this trend is based only on a few exposures. Minor metal analysis indicates there are no significant concentrations of detrimental elements and that cadmium and germanium are possible smelter credits. Appendix C contains copies of all analytical data available for the property.

A sample of galena from Blende was submitted to the University of British Columbia for lead isotope analysis and returned a model age of 1.4 bya (Godwin et al., 1988). The isotopic ratios are nearly identical to those from Hart River and Cord which suggests that the mineralizing event was regional in scale and that Blende may have been a feeder to an eroded stratiform deposit.

Twelve zones of mineralization have been discovered within or adjacent to the fault complex and have been chronologically numbered in the order that they were first discovered by Cyprus Anvil or Archer, Cathro workers. They have been grouped into three packages: the West Zones, which lie west of the Pinguicula Group shale cap; the Central Zones, which lie between the cap and a large landslide on Dean Creek; and, the East Zones which lie east of the landslide.

West Zones

Six specific zones have been recognized (Zones 1,2,5,6,7 and 9) within an area that is approximately 900 m long and varies from 25 to 200 m in width. The location of individual zones is shown, along with assays, on Figure 9 in the

pocket. Even though this is the best exposed and most intensely explored part of the property, the dimensions, average grade and continuity of zones are not known because most mineralized exposures are on cliffs and the rest of the area is covered with a thick layer of talus.

Based on surface work, the widest, most consistent mineralization occurs in Zone 5 adjacent to the Footwall Fault. In 1984 systematic chip sampling of outcrops and hand trenches was conducted over a 750 m strike length along the zone through a vertical range of 200 m and averaged 2.2% Pb, 3.1% Zn and 44.8 g/t Ag across 27.5 m. The real width of the zone is somewhat greater than the sampled width because talus obscured part of the mineralization at several sites. In most exposures, galena and sphalerite are the main sulphide minerals but, at the west end where the zone cuts a diorite dyke, chalcopyrite is common. A 1989 chip sample from the chalcopyrite-rich area returned 3.0% Cu, 8.7% Pb, 1.9% Zn and 1038.8 g/t Ag over 2.8 m. No systematic surface sampling has been done on the other zones but rock specimens and isolated chip samples returned encouraging results with numerous values exceeding 10% Pb+Zn.

In 1988 three holes were drilled in a fan from a single site (as shown on Figure 9) with the intention of testing Zone 5. Surprisingly, the best intersections were obtained from mineralized zones that are obscured at surface by talus and Unit P1 shale cap rocks. These intersections are tentatively correlated to Zones 6 and 7, as shown on the drill sections (Figures 11, 12 and 13 on the following pages). The best assays came from Hole 88-2 which cut obliquely across the mineralized zones and averaged 5.2% Pb, 2.8% Zn and 108.9 g/t Ag over 81.7 m, including 19.8 m that graded 12.3% Pb, 4.4% Zn and 284.8 g/t Ag. All significant intersections are listed in Table 1 on page 20 while complete assays are recorded on the drill logs in Appendix D.



LEGEND

LATE PROTEROZOIC
PINGUICULA GROUP

- P_1 — INTERBEDDED BLACK ARGILLITE, SHALE AND CHERT; MINOR ORANGE WEATHERING DOLOMITE INTERBEDS.

MIDDLE PROTEROZOIC
GILLESPIE LAKE GROUP

- G_2 — ORANGE WEATHERING, MASSIVE GREY TO INTERBEDDED LIGHT GREY AND BLACK ARGILLACEOUS AND STROMATOLITIC DOLOMITE WITH MINOR CHERT INTERBEDS.
- G_1 — LIGHT ORANGE TO MAROON - GREEN WEATHERING INTERBEDDED MAROON AND GREEN SHALE WITH WHITE TO TAN DOLOMITE INTERVALS.

GEOLOGICAL CONTACT

FAULT

3.5, 3.2, 1.7 / 10.7 — Pb(%), Zn(%), Ag (g/t) / METRES

≥ 5 % Pb + Zn

SURFACE MINERALIZATION

Figure 11

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

VERTICAL CROSS SECTION

DDH 88-1

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

0 25 50 100 150 200 m



LEGEND

LATE PROTEROZOIC
PINGUICULA GROUP

P1 — INTERBEDDED BLACK ARGILLITE, SHALE AND CHERT; MINOR ORANGE WEATHERING DOLOMITE INTERBEDS.

MIDDLE PROTEROZOIC
GILLESPIE LAKE GROUP

G2 — ORANGE WEATHERING, MASSIVE GREY TO INTERBEDDED LIGHT GREY AND BLACK ARGILLACEOUS AND STROMATOLITIC DOLOMITE WITH MINOR CHERT INTERBEDS.

G1 — LIGHT ORANGE TO MAROON-GREEN WEATHERING INTERBEDDED MAROON AND GREEN SHALE WITH WHITE TO TAN DOLOMITE INTERVALS.

GEOLOGICAL CONTACT

FAULT

3.5, 3.2, 1.7 / 10.7 — Pb (%), Zn (%), Ag (g/t) / METRES

≥ 5 % Pb + Zn

SURFACE MINERALIZATION

Figure 12

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

VERTICAL CROSS SECTION

DDH 88-2

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

0 25 50 100 150 200 m



Figure 13

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

VERTICAL CROSS SECTION

DDH 88-3

BLENDE PROPERTY

NDU RESOURCES LTD.

BILLITON METALS CANADA INC.

TABLE 1
SIGNIFICANT DRILL INTERSECTIONS
BLENDE PROPERTY

Hole No.	Interval (m) From	To	Width (m)	Pb (%)	Zn (%)	Ag g/t
88-1	**4.3**	**29.0**	**24.7**	**3.5**	**3.3**	**46.5**
includes	4.3	13.7	9.4	4.1	3.9	58.3
	21.3	25.0	3.7	3.3	3.7	44.7
	27.4	29.0	1.6	17.1	13.7	211.5
	43.0	43.9	0.9	7.2	4.2	125.8
	83.5	85.9	2.4	7.9	6.4	190.5
	129.2	132.3	3.1	4.7	2.2	42.2
	143.9	145.4	1.5	3.6	2.3	65.8
	164.9	166.4	1.5	7.1	2.8	105.9
88-2	**8.8**	**90.5**	**81.7**	**5.2**	**2.8**	**108.9**
includes	8.8	10.4	1.6	21.2	6.4	370.3
	11.9	14.9	3.0	7.6	12.0	90.5
	28.6	31.7	3.1	12.2	10.2	163.0
	43.9	50.0	6.1	6.1	3.7	133.8
	51.8	54.9	3.1	3.3	2.1	75.6
	70.7	78.3	7.6	15.4	4.4	426.8
	79.9	90.5	10.6	11.8	5.0	221.5
	207.9	209.7	1.8	3.4	3.6	93.6
88-3	**3.7**	**135.9**	**132.2**	**3.7**	**1.8**	**89.0**
includes	5.2	9.8	4.6	8.9	4.1	154.5
	17.4	18.9	1.5	24.6	11.8	349.7
	29.6	32.6	3.0	6.1	7.4	122.1
	43.3	47.9	4.6	4.5	3.3	97.9
	52.4	53.9	1.5	3.4	4.0	63.1
	57.0	60.0	3.0	6.4	1.8	77.5
	64.6	67.7	3.1	4.8	1.8	110.6
	84.4	85.9	1.5	4.6	1.4	158.0
	89.0	95.1	6.1	9.4	4.5	196.9
	118.0	126.5	8.5	15.3	4.6	550.1
	128.0	135.9	7.9	6.1	3.2	123.9
	227.7	230.7	3.0	2.4	2.8	27.4

Central Zones

The Central Zones (Zones 3, 4, 8 and 10) occur intermittently over an 800 m strike length on a long talus slope between the top of Mount Williams and Dean Creek. Exposure is poor and mineralization is confined to a few float trains and scattered outcrops as shown on Figure 10 in the pocket.

Zones 3, 4 and 8 are a series of subparallel sphalerite-galena veins up to 1 m wide. One of the veins in Zone 4 was sampled in 1989 and returned 1.1% Pb, 14.8% Zn, 19.2 g/t Ag and 0.02% Cu over 0.6 m. Zone 10 lies about 900 m northeast of the fault complex and consists of a 20 by 10 m area containing numerous, 1 to 3 cm in diameter, malachite- and limonite-stained vein fragments, a composite sample of which assayed 1457 g/t Ag with only 0.1% Pb, 0.2% Zn.

East Zones

The East Zones are new discoveries in 1989 and include Zone 11 on the east side of Dean Creek (Figure 10) and Zone 12 in an isolated cirque at the extreme southeast end of the property (Figure 5).

Zone 11 is approximately 300 m long and 200 m wide and consists of hydrozincite-stained, sphalerite- and galena-bearing rock fragments mixed with ferricrete boulders and soil on a gentle, lightly vegetated slope. There are no outcrops in the main part of the zone and bulldozer trenching did not reach bedrock due to frost in the soil. Mineralized boulders up to 2 m in diameter were exposed in the trenches. Selected float specimens returned up to 36.1% Pb, 11.6% Zn and 438.8 g/t Ag, while chip samples across two 1.5 m wide mineralized shear zones exposed on a steep slope at the eastern edge of the zone assayed up to 0.06% Pb, 7.9% Zn and 6.9 g/t Ag.

Zone 12 was discovered during a reconnaissance prospecting traverse and has only received cursory examination. It consists of scattered hydrozincite-stained boulders in two 25 m wide float trains within a broad talus fan at the head of a cirque. The boulders range from 5 to 30 cm in diameter and contain abundant galena and sphalerite in fractures. Specimens returned up to 8.69% Pb, 17.6% Zn, and 31.5 g/t Ag.

GEOCHEMISTRY

General

In 1976 and 1977 the GSC conducted reconnaissance stream sediment sampling in the Blende area as part of a geochemical baseline survey of the Wernecke Mountains. Results of the survey were published as GSC Open File 518. Streams draining the property returned moderate to extremely anomalous values for lead and zinc while other streams within the property's 265 sq km area of interest returned near background values.

In 1989 grid soil sampling was done over approximately 9.2 sq km in the central part of the property and a few reconnaissance prospecting and sampling traverses were conducted around the periphery. Grid sample locations are plotted on Figure 14 in the pocket, while reconnaissance sample locations are shown on the geological and geochemical compilation map, Figure 5.

The grid soil samples were taken along compass and chain controlled, slope corrected lines spaced 100 m apart. The lines were run at right angles between four theodolite-EDM surveyed baselines that are orientated at 125°, subparallel to the fault complex. The baselines were marked at approximately 50 m intervals by 1 m high wood lath pickets bearing aluminum tags inscribed with grid coordinates. Similarly marked 0.5 m high pickets were placed every 20 m along the sample lines. Soil samples were taken at 40 m intervals from "B" or "C" horizon material and the sample number was inscribed on the aluminum tag at the appropriate station picket. Soil was easily obtained even within the coarsest dolomite talus but was scarce on shale scree slopes. Cliffs on north- and west-facing slopes prevented sampling over part of the West Zones.

A total of 2632 soil samples were taken from the grid, while 105 stream sediment and soil samples were collected peripheral to it. All samples were shipped to Chemex Labs Ltd. in North Vancouver, B.C. where they were dried and

sieved through a -80 mesh screen. If the samples contained insufficient fine-grained material, they were sieved again through a -35 mesh screen and then pulverized to -150 mesh. In a few extreme cases, the entire sample was pulverized.

All samples were analyzed for 32 elements by the induced coupled plasma (ICP) technique using a nitric aqua regia digestion. Ninety-nine samples selected from various parts of the grid were also analyzed for gold by neutron activation. Certificates of analysis are presented in Appendix C.

Results

Figure 5 illustrates property geology and mineral occurrences, together with GSC and Archer, Cathro reconnaissance geochemical results for lead and zinc and the areas of anomalous lead response on the soil grid. The reconnaissance sampling shows that the highest stream sediment values (up to 565 ppm lead and 2910 ppm zinc) are from streams draining areas of known mineralization and anomalous grid response. Samples taken in June to the northwest and southeast of the property returned moderately to strongly anomalous values and the claim block was expanded to cover these areas. All other drainages returned near background values.

Figures 15 through 19 in pocket illustrate the grid soil geochemical results for lead, zinc, silver, copper and arsenic, respectively. Based on the regional sampling results and Archer, Cathro's experience elsewhere in the Wernecke Mountains, typical background values and anomalous thresholds for the Blende area are as follows (all values are in ppm).

Threshold	Pb	Zn	Ag	Cu	As
Background	10-50	50-150	0.1-0.5	10-50	10-30
Weakly Anomalous	100	400	1.0	50	50
Moderately Anomalous	200	800	2.0	100	100
Strongly Anomalous	500	2000	5.0	200	200

Sampling outlined a 1000 m wide, 3800 m long belt of weakly to strongly anomalous lead, zinc and silver soil values in the south-central part of the grid plus smaller areas of weak to moderate response throughout the remainder of the sampled area. Summary data for the seven major areas of anomalous lead and zinc soil response are listed in Table 2 on the following page. These areas are referred to as Anomalies A to G for discussion purposes and have not been lettered on the maps. The location of each anomaly is given in Table 2.

The main belt of anomalies consists of two parallel bands that trend obliquely across the fault complex. The northeasterly band coincides with the Central and East Zones and includes Anomalies B, C and D, all of which exhibit lead to zinc ratios of about 0.4:1. The southwesterly band covers the West Zones and includes Anomalies A, E and F which have generally higher lead to zinc ratios. Although the two bands are easily recognized and appear to differ geochemically, there is no geological evidence suggesting that they represent two distinct trends of mineralization. In fact, the strongest anomalies in both bands coincide with known mineralization in the fault complex and the apparent geochemical divergence may be due to fortuitous alignment of mineralization in secondary structures coupled with downhill dispersion. If weakly and moderately anomalous values are ignored, there is a well developed trend that follows the fault complex for the entire 3800 m length of the main anomalous belt, except for background to weakly anomalous values within the Pinguicula Group shale cap on top of Mt. Williams and the landslide area near Dean Creek.

TABLE 2
SUMMARY OF MAJOR SOIL GEOCHEMICAL ANOMALIES ON THE BLENDE GRID

Anomaly	Location	Approximate Dimensions of Pb Anomaly ≥ 500 ppm	Pb:Zn	Pb:Ag	Pb:Cu	Comments
A	West Zones	1300 x 350 m	0.9:1	210:1	30:1	mainly over non-drill tested areas west and southwest of 1988 drill hole collars
B	Central Zone	1000 x 300 m	0.5:1	310:1	20:1	overlying poorly exposed narrow vein structures
C	East Zone	500 x 400 m	0.3:1	240:1	25:1	coincident with numerous poorly exposed float trains and vein structures
D	Centred at 20700N/10250E	100 x 250 m	0.4:1	490:1	40:1	north of fault complex; no known associated mineralization
E	Centred at 19400N/10700E	250 x 100 m	1.4:1	840:1	35:1	minor galena in dolomite talus
F	Centred at 19600N/11250E	100 x 400 m	0.5:1	570:1	40:1	no known associated mineralization
G	between baselines 21000N and 22000N	several anomalies up to 200 x 100 m	1.0:1	560:1	50:1	no known associated mineralization

The West Zones (Anomaly A) produced by far the most impressive response, including a 650 by 150 m area within which more than 60% of the samples exceed the maximum geochemical threshold of 10,000 ppm for lead and zinc. Silver values in the area of maximum response typically exceed 20 ppm and range up to 147 ppm. The 1988 drill holes are on the northern edge of the anomaly and cut mineralized zones which project to surface along cliff faces that could not be grid soil sampled. Thus, nearly all of the anomalous response is from zones along strike or further into the hanging wall that have not yet been explored by drilling. At its west end, the anomaly cuts obliquely across the trend of the fault complex, which suggests the complex may be wider than shown and the Footwall Fault may strike down a talus-filled gully rather than across the slope as currently mapped.

The Central Zones produced an area of anomalous response as large as the West Zones (Anomaly B) but values are lower for all metals. The part of the East Zones covered by the grid (Zone 11) returned high values for lead and zinc on the gentle slopes east of Dean Creek (Anomaly C) but the anomaly terminates at the base of the cliffs to the east where only a few narrow veins have been discovered. Anomalies D, E and F and other weakly to moderately responsive areas in the southern portion of the grid are likely due to downhill dispersion or mineralization in secondary structures, while the smaller anomalies in the northern part of the grid (Anomaly G) are in younger Pinguicula Group units and may have resulted from mineralization in later veins.

Lead values generally correlate with zinc except in the vicinity of some diorite intrusions where moderately anomalous zinc values occur without lead support. These anomalies are probably due to minor sphalerite in small skarns along dolomite-dyke contacts. Lead to zinc ratios show a systematic decrease from west to east along the length of the fault complex.

Silver also correlates well with lead but, because of the thresholds selected, the surface areas of the silver anomalies are about two-thirds to one-half the size of the lead anomalies. Silver to lead ratios are highest over the fault complex.

Copper shows little direct correlation to lead, zinc or silver except in the western half of Anomaly A where it is moderately to strongly anomalous. Other areas of copper response occur along diorite dykes and within the Pinguicula Group where malachite-bearing shear zones have been noted.

Arsenic anomalies coincide with mineralization in both the West and East Zones but the Central Zones returned lower values. Of all the metals, arsenic best delineates the area of copper- and silver-rich mineralization at the west end of Zone 5, probably because of increased tetrahedrite. It is interesting to note that the core of the arsenic anomaly cuts obliquely across the lead and zinc anomalies, suggesting that the copper- and silver-rich mineralization may have been remobilized into a later crosscutting structure when an adjacent diorite dyke was intruded.

The selected samples analyzed for gold returned only background values.

GEOPHYSICS

Magnetic and VLF-EM surveys were conducted between July 10 to 22 by a two-man crew contracted from Delta Geoscience Ltd., using two EDA Omni Plus VLF/mag/gradiometer systems coupled with an Omni Plus base station magnetometer. The work was done on the same grid as the soil sampling with readings at 10 m intervals along the crosslines and baselines.

The VLF-EM survey covered the entire grid and Fraser filtered results are on Figure 20 in the pocket. The magnetic survey was discontinued after about 20 km of readings when it was clear that contrast was low and there was no characteristic response from known mineralization.

Most VLF-EM conductors are associated with faults and topographic linears cutting Pinguicula Group shale in the north and central parts of the grid. The steep, symmetric gradients of the contours suggest that the conductors are narrow, steeply-dipping structures. The data was computer-contoured and automatically biased parallel to the trend of known mineralization, which resulted in north- and northeast-trending conductors appearing as a linear string of intense single point anomalies. Mineralized zones produced only a few weak VLF-EM conductors.

CONCLUSIONS AND DISCUSSION

Soil geochemistry and initial diamond drilling at the Blende property have produced unusually encouraging results from a 6000 m long, up to 200 m wide fault complex and indicate potential for a large open pit deposit of moderate base metal grade with a higher than normal silver content. The best exposed and most anomalous part of the complex strikes along a ridge crest with steep slopes on either side which will effectively reduce the stripping ratio. Preliminary mineralogical studies and trace metal analyses suggest favourable metallurgy.

The next phase of exploration should focus on delineating the limits of mineralization within the fault complex and concentrate on the road-accessible part of the West Zones where a program of 3650 m of diamond drilling in widely spaced holes is recommended. The drilling should be done on section lines spaced 100 m apart, with each line consisting of two holes. The shallow holes will test the northern half of the fault complex while the deeper tier of holes will explore across the entire width of the system.

The 1990 exploration program should commence in mid to late May (depending upon weather) utilizing the camp, bulldozer and diamond drill already on the property. A small, four-wheel drive truck should be flown to the claims for on-site drill support. Expediting and logistical support for the next phase of exploration should again use a contract helicopter based at the road-accessible Sadie Camp north of Keno. If encouraging results are obtained, negotiations should be initiated with the Yukon Government for financial assistance in construction of a summer access road.

REFERENCES

Abbott, J.G. and LeBarge, W.P.
(in press): Yukon Geology and Exploration 1988-89; Indian and Northern Affairs Canada.

Cathro, R.J. and Carne, R.C.
1984: Geological and geochemical report on the Blende 1-15 claims; Archer, Cathro & Associates (1981) Limited (report filed for assessment credit).

Delaney, G.D.
1981: The mid-Proterozoic Wernecke Supergroup, Wernecke Mountains, Yukon Territory; in Proterozoic Basins of Canada, F.H.A. Campbell, ed; Geological Survey of Canada, Paper 81-10, pp.1-23

Eisbacher, G.H.
1981: Sedimentary tectonics and glacial record in the Windermere Supergroup, Mackenzie Mountains, northwestern Canada; Geological Survey of Canada, Paper 80-27.

Geological Survey of Canada
1977: Uranium reconnaissance program national stream sediment and water geochemical reconnaissance data; Geological Survey of Canada, Open File 518.

Green, L.H.
1972: Geology of Nash Creek, Larsen Creek and Dawson map-areas, Yukon Territory; Geological Survey of Canada, Memoir 364.

Godwin, C.I., Gabites, J.E., and Andrew, A.
1988: Leadtable: A galena lead isotope data base for the Canadian Cordillera, with a guide to its use by explorationists; British Columbia Energy, Mines and Petroleum Resources, Paper 1988-4.

Harris, J.F.
(1988): Mineralogical study of samples from the Blende property; Vancouver Petrographics, unpublished report.

Morin, J.A.
1977: A preliminary report on Hart River (116A/10) - a Proterozoic massive sulphide deposit; in Mineral Industry Report 1977, Yukon Territory, pp. 22-24.

Mustard, P.S., Roots, C.F. and Donaldson, J.A.
(in press): Stratigraphy of the Middle Proterozoic Gillespie Lake Group in the southern Wernecke Mountains; Geological Survey of Canada, Paper 90-1A.

Norris, D.K.
1982: Geology, Wind River map area; Geological Survey of Canada, Map 1528A.

Roberts, W. and Dean, P.
1975: Geological and geochemical report on the Will claims; Cyprus Anvil Mining Corporation (report filed for assessment credit).

Roots, C.F.
(in press): Regional mapping in the southern Wernecke Mountains: Geology of eastern Nash Creek map area (106D/8); Geological Survey of Canada, Paper 90-1A.

APPENDIX A

AUTHORS' STATEMENTS OF QUALIFICATIONS

STATEMENT OF QUALIFICATIONS

I, W. Douglas Eaton, geologist, with business addresses in Whitehorse, Yukon Territory and Vancouver, British Columbia and residential address in Burnaby, British Columbia, do hereby delcare:

1. I graduated from the University of British Columbia in 1980 with a B.Sc. majoring in Geological Sciences.
2. From 1971 to present, I have been actively engaged in mineral exploration in Yukon Territory and on June 1, 1981, I became a partner in Archer, Cathro & Associates (1981) Limited.
3. I have personally participated in or supervised the field work reported herein and have interpreted all data resulting from this work.



W. Douglas Eaton, B.A., B.Sc.

STATEMENT OF QUALIFICATIONS

I, Diane Lister, geological engineer, with business addresses in Whitehorse, Yukon Territory and Vancouver, British Columbia and residential address in Vancouver, British Columbia, do hereby certify that:

1. I graduated from the University of British Columbia in 1989 with a B.A.Sc. in geological engineering.
2. From 1981 to present, I have been actively engaged in mineral exploration in the Yukon Territory and am presently employed with Archer, Cathro & Associates (1981) Limited.
3. I have personally participated in and supervised the field work reported herein and have interpreted all data resulting from this work.



D. Lister, B.A.Sc.

APPENDIX B

LIST OF PERSONNEL

ARCHER, CATHRO PERSONNEL
BLENDE PROPERTY, 1989

NAME	POSITION	PERIOD
W. Douglas Eaton	Project Supervisor	June 9 - August 23
Rob Carne	Project Supervisor	June 9 - August 23
Diane Lister	Field Manager/ Geologist	June 17 - August 23
Mike Phillips	Geologist	June 17 - July 12
Stu Miller	Geologist	June 11, 27, July 26 - August 23
Mike Walls	Geologist	June 10 - 27
Dave Parry	Geologist	June 11 - 27
Maggie Dittrick	Geologist	June 11 - 27
Bill Wengzynowski	Prospector	June 10 - 30
Frank Gish	Assistant	June 10 - 15, August 22
Mitchell Couling	Assistant	June 10 - July 26
Mike Gazetas	Assistant	June 21 - July 26
Keith Richmond	Assistant	June 21 - July 26
Mike Mason-Wood	Assistant	July 3 - July 27
Gord MacIntosh	Assistant	August 22
Russell Tough	Cook	June 15 - August 23



APPENDIX

CERTIFICATES OF ANALYSIS

092795

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments:

Page : 1
Total Pages: 1
Date : 01-AUG-88
Invoice # : I-8819021
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819021

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
S 09971	207	--	< 0.002	4.49	11.20	5.96
S 09972	207	--	< 0.002	2.57	4.89	3.04
S 09973	207	--	< 0.002	1.78	4.53	4.34
S 09974	207	--	< 0.002	0.34	1.21	4.13
S 09975	207	--	0.002	0.20	0.54	1.67
S 09976	207	--	< 0.002	1.12	3.11	4.69
S 09977	207	--	< 0.002	0.42	1.17	0.85
S 09978	207	--	< 0.002	0.48	1.19	2.29
S 09979	207	--	0.002	1.33	3.48	4.25
S 09980	207	--	< 0.002	1.28	3.18	3.14
S 09981	207	--	< 0.002	6.17	17.10	13.70
S 09982	207	--	< 0.002	0.76	1.80	1.71
S 09983	207	--	< 0.002	3.67	7.17	4.24
S 09984	207	--	< 0.002	0.35	0.91	0.55
S 09985	207	--	< 0.002	12.80	13.70	4.80
S 09986	207	--	< 0.002	3.18	6.02	6.98
S 09987	207	--	< 0.002	1.37	6.11	2.36
S 09988	207	--	< 0.002	1.09	3.22	2.09
S 09989	207	--	< 0.002	1.92	3.59	2.31
S 09990	207	--	< 0.002	3.09	7.10	2.79
S 09991	207	--	< 0.002	0.07	0.10	0.09
S 09992	207	--	< 0.002	2.04	3.01	0.64

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments:

Page : 1-A
Tot. Pages: 1
Date : 22-JUL-88
Invoice # : I-8819022
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819022

SAMPLE DESCRIPTION	PREP CODE		Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %
S 09971	299	238	0.14	55	< 10	< 0.5	< 2	9.29	47.0	14	3	85	3.71	< 10	6	0.03	< 10	5.64	1245	< 1	0.01
S 09972	299	238	0.09	35	< 10	< 0.5	< 2	12.65	31.5	3	4	67	3.57	< 10	4	0.03	< 10	7.57	1135	2	0.01
S 09973	299	238	0.06	5	< 10	< 0.5	< 2	13.55	56.5	4	4	36	3.35	< 10	4	0.02	< 10	8.18	1295	< 1	0.01
S 09974	299	238	0.09	5	< 10	< 0.5	< 2	>15.00	58.5	3	6	40	1.68	< 10	10	0.02	< 10	9.44	1600	< 1	0.01
S 09975	299	238	0.09	< 5	< 10	< 0.5	< 2	11.45	17.5	3	3	11	0.78	< 10	3	0.05	< 10	6.82	828	< 1	0.01
S 09976	299	238	0.13	30	< 10	< 0.5	< 2	12.35	>99.9	6	5	66	2.37	< 10	10	0.05	< 10	7.44	1205	1	0.01
S 09977	299	238	0.29	15	< 10	< 0.5	< 2	11.55	28.5	2	7	16	1.55	< 10	< 1	0.15	< 10	6.94	691	1	0.01
S 09978	299	238	0.24	15	< 10	< 0.5	< 2	11.80	23.0	7	6	14	1.14	< 10	3	0.11	< 10	7.15	1005	2	0.01
S 09979	299	238	0.07	30	< 10	< 0.5	< 2	13.30	79.0	5	4	27	2.55	< 10	8	0.03	< 10	7.98	1055	2	0.01
S 09980	299	238	0.10	15	< 10	< 0.5	< 2	13.50	62.5	2	4	43	1.47	< 10	3	0.05	< 10	8.13	940	1	0.01
S 09981	299	238	0.13	120	< 10	< 0.5	12	5.84	>99.9	16	5	310	3.72	< 10	26	0.05	< 10	3.23	764	7	0.01
S 09982	299	238	0.03	< 5	< 10	< 0.5	< 2	>15.00	30.0	< 1	4	17	1.08	< 10	5	0.01	< 10	10.30	796	< 1	0.02
S 09983	299	238	0.07	35	10	< 0.5	< 2	10.70	74.0	4	7	51	1.58	< 10	5	0.04	< 10	6.25	1015	1	0.01
S 09984	299	238	0.03	< 5	< 10	< 0.5	< 2	14.50	11.0	< 1	4	12	0.85	< 10	1	0.02	< 10	8.68	566	1	0.01
S 09985	299	238	0.07	75	< 10	< 0.5	< 2	12.00	95.5	7	14	250	2.90	< 10	12	0.05	< 10	6.62	1135	5	0.01
S 09986	299	238	0.11	80	10	< 0.5	< 2	9.48	>99.9	26	14	250	2.36	< 10	21	0.09	< 10	5.07	1350	3	0.01
S 09987	299	238	0.08	30	< 10	< 0.5	< 2	12.60	44.5	14	10	96	1.70	< 10	5	0.06	< 10	7.30	1105	< 1	0.01
S 09988	299	238	0.02	15	< 10	< 0.5	< 2	>15.00	36.0	4	10	54	1.26	< 10	4	0.01	< 10	9.44	790	1	0.01
S 09989	299	238	0.07	10	< 10	< 0.5	< 2	12.25	41.5	7	6	113	1.33	< 10	4	0.05	< 10	7.29	834	< 1	0.01
S 09990	299	238	0.06	35	< 10	< 0.5	< 2	13.20	49.5	21	10	269	2.01	< 10	6	0.04	< 10	7.53	1490	2	0.01
S 09991	299	238	0.06	80	< 10	< 0.5	< 2	>15.00	1.0	17	11	35	6.49	< 10	< 1	0.04	< 10	9.18	1345	< 1	0.02
S 09992	299	238	0.04	< 5	< 10	< 0.5	< 2	14.20	14.0	7	15	103	1.13	< 10	< 1	0.03	< 10	8.68	636	1	0.01

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments:

Page : 1-B
Total Pages: 1
Date : 22-JUL-88
Invoice # : I-8819022
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819022

SAMPLE DESCRIPTION	PREP CODE		Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 09971	299	238	18	270	>10000	50	2	27	< 0.01	< 10	< 10	4	80	>10000
S 09972	299	238	1	180	>10000	50	1	35	< 0.01	< 10	< 10	3	55	>10000
S 09973	299	238	4	180	>10000	40	1	36	< 0.01	< 10	< 10	3	65	>10000
S 09974	299	238	3	200	>10000	< 5	1	40	< 0.01	< 10	< 10	3	60	>10000
S 09975	299	238	3	100	3800	10	1	24	< 0.01	< 10	< 10	1	20	>10000
S 09976	299	238	7	250	>10000	10	2	28	< 0.01	< 10	< 10	5	65	>10000
S 09977	299	238	13	180	>10000	10	3	29	< 0.01	< 10	< 10	5	20	7710
S 09978	299	238	14	170	>10000	10	2	23	< 0.01	< 10	< 10	4	40	>10000
S 09979	299	238	7	230	>10000	25	1	20	< 0.01	< 10	< 10	4	65	>10000
S 09980	299	238	8	190	>10000	25	1	21	< 0.01	< 10	< 10	3	40	>10000
S 09981	299	238	21	490	>10000	115	1	23	< 0.01	< 10	< 10	3	130	>10000
S 09982	299	238	2	90	>10000	25	1	24	< 0.01	< 10	< 10	1	30	>10000
S 09983	299	238	7	300	>10000	110	1	20	< 0.01	< 10	< 10	2	65	>10000
S 09984	299	238	< 1	60	9230	15	1	27	< 0.01	< 10	< 10	3	10	5200
S 09985	299	238	22	230	>10000	1165	1	25	< 0.01	< 10	< 10	3	85	>10000
S 09986	299	238	40	460	>10000	145	2	31	< 0.01	< 10	< 10	4	95	>10000
S 09987	299	238	21	210	>10000	40	2	90	< 0.01	< 10	< 10	4	45	>10000
S 09988	299	238	15	110	>10000	40	1	72	< 0.01	< 10	< 10	3	40	>10000
S 09989	299	238	16	200	>10000	50	1	108	< 0.01	< 10	< 10	1	45	>10000
S 09990	299	238	31	200	>10000	75	2	126	< 0.01	< 10	< 10	2	55	>10000
S 09991	299	238	28	40	870	10	1	45	< 0.01	< 10	< 10	4	55	875
S 09992	299	238	17	120	>10000	120	1	62	< 0.01	< 10	< 10	3	15	6040

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments:

Page : 1
Total Pages: 2
Date : 06-AUG-88
Invoice # : I-8819567
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819567

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
S 09171	207	---	< 0.002	0.34	0.95	1.39
S 09172	207	---	< 0.002	0.17	0.39	1.00
S 09173	207	---	< 0.002	0.16	0.23	0.14
S 09174	207	---	< 0.002	0.13	0.44	0.61
S 09175	207	---	< 0.002	0.44	1.30	0.42
S 09176	207	---	< 0.002	6.27	15.30	7.29
S 09177	207	---	< 0.002	3.24	9.00	13.20
S 09178	207	---	< 0.002	0.31	0.76	2.53
S 09179	207	---	< 0.002	0.35	0.91	1.01
S 09180	207	---	< 0.002	0.36	0.85	0.82
S 09181	207	---	< 0.002	0.38	0.70	0.52
S 09182	207	---	< 0.002	0.79	1.68	1.18
S 09183	207	---	< 0.002	0.67	1.57	2.00
S 09184	207	---	< 0.002	0.74	1.17	4.92
S 09185	207	---	< 0.002	1.95	3.13	1.83
S 09186	207	---	< 0.002	3.53	5.72	2.92
S 09187	207	---	< 0.002	6.56	10.20	4.69
S 09188	207	---	< 0.002	4.05	6.30	4.42
S 09189	207	---	< 0.002	1.46	2.17	2.96
S 09190	207	---	< 0.002	0.60	0.90	0.46
S 09191	207	---	< 0.002	2.51	3.29	1.76
S 09192	207	---	< 0.002	1.90	3.36	2.53
S 09193	207	---	< 0.002	0.87	1.87	2.15
S 09194	207	---	< 0.002	1.21	2.40	2.03
S 09195	207	---	< 0.002	0.51	1.02	0.41
S 09196	207	---	< 0.002	0.31	0.65	0.13
S 09197	207	---	< 0.002	0.19	0.36	0.08
S 09198	207	---	< 0.002	0.46	0.77	0.13
S 09199	207	---	< 0.002	0.13	0.21	0.10
S 09200	207	---	< 0.002	0.24	0.40	0.35
S 09601	207	---	< 0.002	0.51	0.86	0.37
S 09602	207	---	< 0.002	0.70	1.25	0.33
S 09603	207	---	< 0.002	4.00	5.56	1.35
S 09604	207	---	< 0.002	13.60	17.40	3.99
S 09605	207	---	< 0.002	9.62	12.10	3.15
S 09606	207	---	< 0.002	15.30	18.30	6.12
S 09607	207	---	< 0.002	19.80	23.4	7.55
S 09608	207	---	< 0.002	0.57	0.72	0.88
S 09609	207	---	< 0.002	3.88	5.44	3.56
S 09610	207	---	< 0.002	2.30	4.06	4.99

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments:

Date : 06-AUG-88
Invoice # : I-8819567
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819567

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
S 09611	207	--	0.002	8.46	13.80	7.67
S 09612	207	--	< 0.002	12.10	20.3	7.17
S 09613	207	--	< 0.002	7.15	13.90	2.55
S 09614	207	--	< 0.002	3.91	8.37	2.25
S 09615	207	--	< 0.002	7.44	16.60	6.20
S 09616	207	--	< 0.002	0.25	0.59	3.26
S 09617	207	--	< 0.002	0.28	0.63	0.34
S 09618	207	--	< 0.002	0.45	1.01	0.33
S 09993	207	--	< 0.002	10.80	21.2	6.41
S 09994	207	--	< 0.002	0.31	0.84	0.91
S 09995	207	--	0.007	1.43	5.42	7.74
S 09996	207	--	< 0.002	3.85	9.82	16.30
S 09997	207	--	< 0.002	0.47	1.51	1.86
S 09998	207	--	< 0.002	0.52	1.63	0.81
S 09999	207	--	< 0.002	0.07	0.17	0.41
S 10000	207	--	< 0.002	< 0.01	0.03	0.08

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 1-A
Total Pages: 2
Date : 04-AUG-88
Invoice # : I-8819568
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819568

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 09171	299	238	0.08	18.2	< 5	< 10	2.5	30	>15.00	18.0	21	< 1	52	3.33	20	< 1	0.06	80	11.05	944	5
S 09172	299	238	0.08	16.0	< 5	< 10	< 0.5	84	>15.00	22.5	22	< 1	28	1.15	10	< 1	0.10	80	12.00	881	2
S 09173	299	238	0.09	11.6	< 5	< 10	< 0.5	38	>15.00	11.0	11	< 1	46	1.15	10	< 1	0.06	80	12.60	797	13
S 09174	299	238	0.08	11.8	< 5	< 10	< 0.5	26	>15.00	18.5	10	8	9	1.00	< 10	< 1	< 0.01	80	11.80	700	1
S 09175	299	238	0.08	21.6	< 5	< 10	< 0.5	< 2	>15.00	9.0	22	8	16	1.10	10	< 1	< 0.01	80	11.50	749	1
S 09176	299	238	0.08	>200	< 5	< 10	2.5	48	11.60	>99.9	21	< 1	85	3.17	20	< 1	0.03	70	7.05	1440	5
S 09177	299	238	0.14	114.0	45	10	1.5	20	7.26	>99.9	21	< 1	348	2.56	30	7	0.06	70	4.48	881	4
S 09178	299	238	0.20	17.6	< 5	10	< 0.5	26	14.50	34.0	22	8	32	1.63	30	32	0.10	90	8.84	1140	2
S 09179	299	238	0.16	18.4	< 5	10	< 0.5	44	>15.00	32.0	22	< 1	15	1.17	10	< 1	0.13	90	10.70	704	2
S 09180	299	238	0.15	22.6	< 5	10	< 0.5	66	>15.00	18.0	10	8	12	1.23	20	< 1	0.05	80	11.30	662	2
S 09181	299	238	0.15	21.8	< 5	10	< 0.5	40	>15.00	21.0	10	< 1	17	1.25	10	< 1	0.10	80	11.60	623	2
S 09182	299	238	0.16	33.8	< 5	10	< 0.5	84	>15.00	29.5	10	< 1	14	1.19	10	< 1	0.16	90	10.75	636	2
S 09183	299	238	0.18	29.2	< 5	10	< 0.5	34	>15.00	49.5	10	36	93	1.38	30	13	0.22	80	9.97	823	2
S 09184	299	238	0.10	35.0	10	< 10	< 0.5	44	13.95	>99.9	10	35	43	1.54	40	21	0.09	80	8.25	946	2
S 09185	299	238	0.13	70.8	< 5	10	< 0.5	64	12.35	41.5	10	< 1	19	1.16	10	< 1	0.06	80	7.41	530	2
S 09186	299	238	0.08	130.5	< 5	30	< 0.5	< 2	14.35	66.5	11	26	37	1.26	20	< 1	0.04	90	8.71	585	2
S 09187	299	238	0.10	>200	< 5	< 10	2.0	74	12.80	95.0	10	117	117	2.31	20	< 1	0.02	80	7.78	720	4
S 09188	299	238	0.14	130.0	< 5	10	< 0.5	44	13.55	83.5	10	< 1	68	1.71	10	< 1	0.03	80	8.06	704	2
S 09189	299	238	0.18	56.8	< 5	10	< 0.5	18	>15.00	57.0	10	17	30	1.51	10	< 1	0.07	80	10.25	739	2
S 09190	299	238	0.16	29.2	< 5	10	< 0.5	40	>15.00	10.0	< 1	< 1	11	1.24	< 10	10	0.08	80	11.50	720	13
S 09191	299	238	0.15	93.8	< 5	10	< 0.5	26	>15.00	37.5	22	8	42	1.27	30	< 1	0.09	80	11.25	668	2
S 09192	299	238	0.18	76.2	< 5	10	< 0.5	< 2	>15.00	49.5	< 1	8	45	1.67	20	< 1	0.10	90	10.95	910	2
S 09193	299	238	0.19	43.4	< 5	10	< 0.5	30	>15.00	36.5	10	< 1	41	1.39	< 10	< 1	0.09	80	11.55	716	2
S 09194	299	238	0.15	52.6	< 5	10	< 0.5	64	>15.00	40.0	< 1	< 1	31	1.53	10	5	0.05	80	10.10	672	2
S 09195	299	238	0.37	30.0	< 5	10	< 0.5	48	14.35	13.5	22	< 1	28	1.14	10	< 1	0.22	100	8.82	613	2
S 09196	299	238	0.23	18.6	< 5	10	< 0.5	40	>15.00	5.5	22	< 1	17	1.12	20	< 1	0.12	90	10.10	681	13
S 09197	299	238	0.15	19.6	< 5	10	< 0.5	22	>15.00	7.5	11	< 1	19	0.98	10	< 1	0.11	90	11.15	623	< 1
S 09198	299	238	0.11	21.4	70	10	< 0.5	56	>15.00	2.5	11	8	19	0.97	20	3	0.07	80	11.85	633	13
S 09199	299	238	0.15	14.6	50	10	< 0.5	< 2	>15.00	5.0	11	17	15	1.01	20	< 1	0.11	90	12.00	642	13
S 09200	299	238	0.10	20.2	< 5	< 10	< 0.5	58	>15.00	6.5	< 1	8	17	1.21	10	< 1	0.03	90	12.20	832	13
S 09601	299	238	0.11	29.0	< 5	< 10	< 0.5	80	>15.00	5.5	22	17	23	1.38	< 10	< 1	0.11	80	11.65	1105	2
S 09602	299	238	0.22	37.0	< 5	10	< 0.5	< 2	>15.00	15.5	10	8	20	1.41	20	26	0.24	90	10.05	946	2
S 09603	299	238	0.21	142.5	< 5	10	< 0.5	34	13.80	30.0	10	< 1	45	1.37	20	13	0.13	90	8.59	849	2
S 09604	299	238	0.08	>200	< 5	< 10	< 0.5	44	11.20	74.5	10	< 1	90	1.61	20	8	0.03	70	6.44	772	2
S 09605	299	238	0.12	>200	< 5	< 10	< 0.5	54	13.25	70.5	< 1	< 1	90	1.43	20	< 1	0.03	90	8.30	772	2
S 09606	299	238	0.07	>200	155	< 10	1.5	< 2	8.60	>99.9	10	< 1	160	2.67	< 10	< 1	< 0.01	70	5.33	1080	4
S 09607	299	238	0.14	>200	< 5	10	< 0.5	38	6.68	>99.9	10	< 1	204	2.08	20	< 1	0.02	60	4.17	1120	3
S 09608	299	238	0.20	28.0	< 5	10	< 0.5	< 2	>15.00	54.5	< 1	17	29	1.53	20	20	0.10	90	9.70	1150	8
S 09609	299	238	0.13	134.5	< 5	10	< 0.5	46	14.35	88.5	10	8	84	1.76	20	< 1	0.03	90	8.83	1140	3
S 09610	299	238	0.16	74.8	< 5	< 10	< 0.5	50	12.90	>99.9	22	8	89	1.64	40	< 1	0.02	90	8.11	1225	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 1-B
Total Pages: 2
Date : 04-AUG-88
Invoice # : I-8819568
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819568

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	V ppm	W ppm	Zn ppm
S 09171	299	238	0.24	29	250	8510	70	3	28	< 0.01	< 10	< 1	< 5	>10000
S 09172	299	238	0.24	< 1	440	3770	55	3	29	< 0.01	< 10	2	< 5	9400
S 09173	299	238	0.25	< 1	450	2270	75	3	30	< 0.01	< 10	< 1	< 5	1535
S 09174	299	238	0.22	< 1	150	4300	60	3	32	< 0.01	< 10	6	< 5	5680
S 09175	299	238	0.24	20	290	>10000	70	3	33	< 0.01	< 10	4	35	4290
S 09176	299	238	0.23	< 1	220	>10000	320	3	24	< 0.01	< 10	5	120	>10000
S 09177	299	238	0.23	45	540	>10000	260	3	22	< 0.01	< 10	8	165	>10000
S 09178	299	238	0.22	17	270	7480	110	6	33	< 0.01	< 10	10	35	>10000
S 09179	299	238	0.21	< 1	200	8460	70	3	35	< 0.01	< 10	< 1	< 5	>10000
S 09180	299	238	0.25	7	510	8520	100	3	35	< 0.01	< 10	7	20	7970
S 09181	299	238	0.23	64	380	7000	125	5	34	< 0.01	< 10	5	< 5	5440
S 09182	299	238	0.23	45	160	>10000	110	5	36	< 0.01	< 10	7	20	>10000
S 09183	299	238	0.26	5	390	>10000	185	5	45	< 0.01	30	12	30	>10000
S 09184	299	238	0.22	31	290	>10000	225	4	31	< 0.01	40	13	20	>10000
S 09185	299	238	0.22	< 1	240	>10000	500	4	32	< 0.01	< 10	4	< 5	>10000
S 09186	299	238	0.23	< 1	370	>10000	800	3	31	< 0.01	40	12	50	>10000
S 09187	299	238	0.22	54	200	>10000	820	4	29	< 0.01	< 10	10	95	>10000
S 09188	299	238	0.23	< 1	180	>10000	935	3	31	< 0.01	< 10	8	80	>10000
S 09189	299	238	0.23	< 1	230	>10000	270	4	34	< 0.01	< 10	3	30	>10000
S 09190	299	238	0.23	8	240	8570	100	3	36	< 0.01	< 10	2	< 5	4930
S 09191	299	238	0.25	6	210	>10000	270	4	36	< 0.01	10	5	20	>10000
S 09192	299	238	0.24	29	240	>10000	255	5	41	< 0.01	< 10	4	55	>10000
S 09193	299	238	0.25	< 1	270	>10000	185	4	35	< 0.01	< 10	< 1	55	>10000
S 09194	299	238	0.24	11	380	>10000	100	3	35	< 0.01	< 10	7	< 5	>10000
S 09195	299	238	0.25	< 1	150	>10000	60	6	39	< 0.01	< 10	8	< 5	4350
S 09196	299	238	0.23	8	120	6400	75	4	39	< 0.01	< 10	8	< 5	1410
S 09197	299	238	0.23	23	130	3260	55	3	35	< 0.01	< 10	3	20	826
S 09198	299	238	0.22	< 1	160	7240	75	3	34	< 0.01	10	3	70	1420
S 09199	299	238	0.23	23	210	2030	40	3	38	< 0.01	60	1	< 5	1055
S 09200	299	238	0.25	< 1	200	3840	150	3	36	< 0.01	< 10	8	< 5	3490
S 09601	299	238	0.26	< 1	360	8090	60	3	38	< 0.01	< 10	8	< 5	3590
S 09602	299	238	0.23	26	180	>10000	70	6	42	< 0.01	10	7	30	6470
S 09603	299	238	0.22	< 1	330	>10000	350	6	36	< 0.01	< 10	8	< 5	>10000
S 09604	299	238	0.21	4	170	>10000	3290	3	27	< 0.01	70	7	95	>10000
S 09605	299	238	0.25	20	310	>10000	2050	3	34	< 0.01	10	9	55	>10000
S 09606	299	238	0.22	3	170	>10000	2200	3	35	< 0.01	< 10	7	45	>10000
S 09607	299	238	0.21	49	220	>10000	1435	2	38	< 0.01	< 10	9	150	>10000
S 09608	299	238	0.24	8	580	7150	135	5	47	< 0.01	< 10	4	< 5	9040
S 09609	299	238	0.23	8	400	>10000	275	3	48	< 0.01	< 10	10	55	>10000
S 09610	299	238	0.31	8	410	>10000	155	3	45	< 0.01	20	8	60	>10000

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Date : 04-AUG-88
Invoice # : I-8819568
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819568

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 09611	299	238	0.08	>200	120	10	< 0.5	52	10.20	>99.9	10	8	342	1.73	30	< 1	< 0.01	80	6.33	798	3
S 09612	299	238	0.10	>200	400	< 10	< 0.5	< 2	9.36	>99.9	10	8	171	1.81	10	< 1	0.01	70	5.63	585	3
S 09613	299	238	0.07	>200	305	< 10	< 0.5	54	13.65	49.0	10	< 1	129	1.33	10	< 1	0.08	80	8.41	630	2
S 09614	299	238	0.08	124.0	110	< 10	< 0.5	22	14.20	46.0	10	8	166	1.58	10	< 1	0.07	90	8.87	678	2
S 09615	299	238	0.07	>200	440	< 10	2.0	36	11.55	>99.9	21	35	270	3.40	10	< 1	< 0.01	70	6.96	929	5
S 09616	299	238	0.28	18.2	155	20	< 0.5	36	11.90	72.0	22	17	78	1.92	10	< 1	0.18	90	7.01	1185	14
S 09617	299	238	0.19	20.0	< 5	10	< 0.5	14	13.80	11.0	22	17	87	1.33	20	< 1	0.07	90	8.37	859	2
S 09618	299	238	0.31	22.4	< 5	10	< 0.5	< 2	11.10	10.0	22	26	100	1.46	20	< 1	0.29	80	6.59	762	2
S 09993	299	238	0.16	>200	85	< 10	6.0	< 2	7.16	>99.9	19	35	494	10.65	20	< 1	0.07	70	4.41	1170	< 1
S 09994	299	238	0.17	16.8	< 5	< 10	< 0.5	< 2	>15.00	41.5	22	< 1	40	1.84	10	< 1	0.07	80	11.80	1680	3
S 09995	299	238	0.13	48.8	< 5	< 10	5.0	< 2	12.95	56.0	20	< 1	133	5.40	30	< 1	0.07	80	8.05	2120	9
S 09996	299	238	0.12	129.5	< 5	20	6.0	20	8.15	>99.9	20	< 1	141	7.30	20	8	< 0.01	70	5.07	1470	12
S 09997	299	238	0.12	21.6	< 5	10	< 0.5	< 2	>15.00	39.5	10	8	35	1.87	30	22	0.05	90	10.50	946	14
S 09998	299	238	0.19	22.6	25	10	1.5	52	>15.00	18.0	10	8	43	3.77	10	< 1	0.05	90	10.40	945	< 1
S 09999	299	238	0.10	12.4	< 5	< 10	< 0.5	68	>15.00	18.5	< 1	< 1	22	1.54	10	< 1	0.07	80	12.10	939	14
S 10000	299	238	0.09	10.4	< 5	< 10	< 0.5	12	>15.00	9.5	< 1	17	27	1.06	20	< 1	0.05	80	12.75	839	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Date : 04-AUG-88
Invoice # : I-8819568
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819568

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	V ppm	W ppm	Zn ppm
S 09611	299	238	0.23	< 1	290	>10000	1135	4	35	< 0.01	10	8	130	>10000
S 09612	299	238	0.21	16	200	>10000	2070	3	31	< 0.01	< 10	8	135	>10000
S 09613	299	238	0.22	< 1	310	>10000	590	3	43	< 0.01	< 10	6	75	>10000
S 09614	299	238	0.24	< 1	170	>10000	470	3	35	< 0.01	< 10	4	10	>10000
S 09615	299	238	0.24	39	250	>10000	620	3	31	< 0.01	< 10	6	70	>10000
S 09616	299	238	0.24	14	320	5870	90	6	70	< 0.01	< 10	11	5	>10000
S 09617	299	238	0.22	20	390	6000	90	4	75	< 0.01	< 10	5	40	3540
S 09618	299	238	0.22	14	530	9930	110	6	78	< 0.01	40	12	60	3530
S 09993	299	238	0.22	8	230	>10000	600	4	21	< 0.01	< 10	11	150	>10000
S 09994	299	238	0.25	< 1	270	8230	155	3	40	< 0.01	< 10	5	< 5	9670
S 09995	299	238	0.27	26	270	>10000	285	4	29	< 0.01	< 10	12	70	>10000
S 09996	299	238	0.24	30	510	>10000	235	3	20	< 0.01	< 10	12	220	>10000
S 09997	299	238	0.37	13	220	>10000	85	3	36	< 0.01	< 10	8	70	>10000
S 09998	299	238	0.41	9	250	>10000	90	4	31	< 0.01	< 10	8	35	7130
S 09999	299	238	0.32	< 1	190	1515	85	3	29	< 0.01	50	6	30	4220
S 10000	299	238	0.38	17	100	348	70	3	29	< 0.01	< 10	11	< 5	901

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NIDU (BLENDE)
Comments:

Page : 1
Total Pages: 1
Date : 16-AUG-88
Invoice # : I-8819937
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8819937

SAMPLE DESCRIPTION	PREP CODE		WO3 NAA %									
S 09981	214	--	< 0.001									

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page : 1
Tot. Pages: 1
Date : 08-AUG-88
Invoice # : I-8820072
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8820072

SAMPLE DESCRIPTION	PREP CODE		Pb %	Zn %	Ag oz/T
S 09619	207	--	0.03	0.05	< 0.01
S 09620	207	--	0.03	0.01	0.01
S 09621	207	--	0.03	0.01	0.01
S 09622	207	--	0.03	0.02	0.01
S 09623	207	--	0.03	0.02	< 0.01
S 09624	207	--	0.01	0.04	< 0.01
S 09625	207	--	0.02	0.04	< 0.01
S 09626	207	--	0.55	0.11	0.15
S 09627	207	--	0.40	0.08	0.13
S 09628	207	--	0.25	0.05	0.20
S 09629	207	--	0.41	0.07	0.38
S 09630	207	--	0.11	0.06	0.07
S 09631	207	--	0.23	0.08	0.11
S 09632	207	--	0.07	0.05	0.06
S 09633	207	--	0.10	0.04	0.06
S 09634	207	--	0.63	0.19	0.19
S 09635	207	--	0.78	0.19	0.29
S 09636	207	--	0.16	0.13	0.10
S 09637	207	--	0.02	0.01	< 0.01
S 09638	207	--	0.01	0.01	< 0.01
S 09639	207	--	0.01	0.01	< 0.01
S 09640	207	--	0.01	0.01	0.02
S 09641	207	--	0.02	0.01	0.01
S 09642	207	--	0.01	0.01	< 0.01
S 09643	207	--	0.02	0.01	< 0.01
S 09644	207	--	0.02	0.01	0.01
S 09645	207	--	0.02	0.01	< 0.01
S 09646	207	--	0.01	< 0.01	< 0.01
S 09647	207	--	0.02	0.01	< 0.01
S 09648	207	--	0.03	0.02	0.04
S 09649	207	--	0.08	1.04	0.03
S 09650	207	--	0.11	0.82	0.07
S 09672	207	--	2.03	1.41	0.29
S 09673	207	--	1.08	0.35	0.16
S 09674	207	--	1.90	1.34	0.29
S 09675	207	--	1.48	0.67	0.26
S 09676	207	--	0.98	0.33	0.15
S 09677	207	--	0.64	0.41	0.14
S 09678	207	--	0.50	0.33	0.19

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page : 1-A
Total Pages: 1
Date : 11-AUG-88
Invoice # : I-8820073
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8820073

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 09619	299	238	0.84	< 0.2	20	20	< 0.5	< 2	8.97	0.5	1	22	6	1.64	< 10	< 1	0.57	< 10	5.53	787	2
S 09620	299	238	1.16	< 0.2	< 5	30	0.5	< 2	8.46	1.5	1	17	10	1.11	< 10	< 1	0.78	< 10	5.42	454	1
S 09621	299	238	1.76	< 0.2	15	40	0.5	< 2	8.47	< 0.5	1	14	15	1.02	< 10	< 1	1.17	< 10	5.53	426	< 1
S 09622	299	238	1.88	< 0.2	5	40	0.5	< 2	8.23	0.5	1	16	17	1.03	< 10	< 1	1.25	< 10	5.35	429	< 1
S 09623	299	238	1.43	< 0.2	5	30	0.5	8	8.99	0.5	1	16	11	1.18	< 10	< 1	0.95	< 10	5.74	506	2
S 09624	299	238	0.74	< 0.2	40	20	< 0.5	4	9.25	0.5	1	19	15	1.40	< 10	< 1	0.52	< 10	5.69	900	< 1
S 09625	299	238	0.79	< 0.2	30	20	< 0.5	6	10.30	0.5	1	20	9	1.26	< 10	3	0.53	< 10	6.44	695	< 1
S 09626	299	238	0.18	2.8	< 5	< 10	< 0.5	12	13.80	2.5	1	16	12	1.34	< 10	< 1	0.13	< 10	8.55	1140	< 1
S 09627	299	238	0.14	2.6	< 5	< 10	< 0.5	8	14.35	2.0	2	15	9	0.91	< 10	< 1	0.09	< 10	9.14	769	< 1
S 09628	299	238	0.12	4.6	10	< 10	< 0.5	< 2	14.50	1.5	2	14	49	0.87	< 10	4	0.07	< 10	9.31	742	1
S 09629	299	238	0.11	8.6	< 5	< 10	< 0.5	6	11.80	1.0	3	17	88	0.83	< 10	< 1	0.07	< 10	7.47	568	< 1
S 09630	299	238	0.65	< 0.2	30	10	0.5	10	12.50	< 0.5	3	13	15	0.87	< 10	< 1	0.43	< 10	7.89	602	< 1
S 09631	299	238	0.87	1.4	< 5	20	0.5	2	11.50	1.5	3	18	20	0.90	< 10	< 1	0.57	< 10	7.29	612	< 1
S 09632	299	238	0.91	0.6	5	20	0.5	12	12.55	0.5	3	16	16	0.93	< 10	< 1	0.58	< 10	7.89	601	< 1
S 09633	299	238	0.73	0.4	< 5	10	< 0.5	14	13.25	0.5	3	14	8	0.84	< 10	< 1	0.46	< 10	8.44	599	< 1
S 09634	299	238	0.34	4.0	< 5	< 10	< 0.5	10	14.95	4.0	3	13	21	0.89	< 10	< 1	0.22	< 10	9.43	724	< 1
S 09635	299	238	0.14	7.4	< 5	< 10	< 0.5	10	>15.00	3.5	3	11	20	0.99	< 10	< 1	0.09	< 10	9.50	718	< 1
S 09636	299	238	1.24	1.4	35	60	0.5	6	9.16	3.0	2	15	26	1.09	< 10	< 1	0.80	< 10	5.77	511	< 1
S 09637	299	238	1.03	< 0.2	< 5	30	0.5	16	8.32	1.5	2	20	6	1.12	< 10	< 1	0.68	< 10	5.23	475	2
S 09638	299	238	2.38	< 0.2	< 5	50	1.0	14	7.41	< 0.5	2	22	4	1.51	< 10	< 1	1.53	< 10	4.80	423	< 1
S 09639	299	238	2.06	< 0.2	20	60	< 0.5	8	7.56	< 0.5	< 1	22	7	1.22	< 10	4	1.31	< 10	4.80	452	1
S 09640	299	238	1.64	< 0.2	< 5	40	< 0.5	2	7.91	< 0.5	< 1	20	6	1.07	< 10	< 1	1.05	< 10	4.95	465	3
S 09641	299	238	1.22	< 0.2	25	30	< 0.5	6	7.81	< 0.5	< 1	18	15	1.03	< 10	7	0.79	< 10	4.86	452	1
S 09642	299	238	1.12	< 0.2	20	30	< 0.5	8	9.43	< 0.5	< 1	17	8	1.10	< 10	12	0.72	< 10	5.81	541	1
S 09643	299	238	0.98	< 0.2	< 5	20	< 0.5	2	9.21	< 0.5	< 1	14	8	0.96	< 10	6	0.63	< 10	5.73	482	1
S 09644	299	238	0.82	0.4	< 5	20	< 0.5	4	9.93	< 0.5	< 1	14	22	0.95	< 10	7	0.53	< 10	6.20	499	< 1
S 09645	299	238	1.01	< 0.2	< 5	20	< 0.5	10	10.40	0.5	< 1	14	7	0.98	< 10	10	0.66	< 10	6.55	495	1
S 09646	299	238	0.77	< 0.2	25	20	< 0.5	8	11.10	< 0.5	< 1	16	6	1.03	< 10	15	0.51	< 10	6.91	523	3
S 09647	299	238	1.38	< 0.2	< 5	30	< 0.5	6	10.75	0.5	< 1	15	12	1.13	< 10	6	0.88	< 10	6.70	502	< 1
S 09648	299	238	1.46	< 0.2	< 5	30	< 0.5	6	9.67	< 0.5	< 1	14	7	1.01	< 10	2	0.93	< 10	6.13	475	1
S 09649	299	238	1.77	0.4	35	40	< 0.5	10	8.98	15.5	< 1	15	34	1.13	< 10	12	1.11	< 10	5.69	487	< 1
S 09650	299	238	1.89	0.6	40	30	< 0.5	6	8.58	12.5	29	15	21	1.85	< 10	12	1.17	< 10	5.15	1100	1
S 09672	299	238	1.05	6.6	< 5	20	< 0.5	10	11.15	20.5	< 1	15	25	1.40	< 10	4	0.65	< 10	6.75	1115	< 1
S 09673	299	238	0.39	3.4	< 5	10	< 0.5	6	13.00	6.0	< 1	14	30	1.72	< 10	8	0.23	< 10	7.63	1510	1
S 09674	299	238	0.22	7.2	< 5	< 10	< 0.5	10	12.65	20.0	< 1	12	80	1.83	< 10	6	0.13	< 10	7.35	1905	3
S 09675	299	238	0.32	6.4	30	< 10	< 0.5	8	12.60	9.5	< 1	8	23	1.32	< 10	< 1	0.19	< 10	7.61	1205	< 1
S 09676	299	238	0.39	3.8	5	< 10	< 0.5	14	13.60	5.0	< 1	10	14	1.15	< 10	3	0.23	< 10	8.35	965	< 1
S 09677	299	238	0.42	3.4	20	< 10	< 0.5	12	12.50	5.5	< 1	14	31	1.06	< 10	7	0.25	< 10	7.74	912	3
S 09678	299	238	0.38	5.6	< 5	10	< 0.5	6	12.25	5.0	< 1	14	41	0.77	< 10	3	0.24	< 10	7.69	644	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page : 1-B
Tot. . ges: 1
Date : 11-AUG-88
Invoice # : I-8820073
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8820073

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 09619	299	238	0.01	10	310	176	5	3	96	0.01	< 10	< 10	13	20	391
S 09620	299	238	0.01	11	340	258	5	4	94	0.02	< 10	< 10	18	10	52
S 09621	299	238	0.02	13	300	248	10	5	88	0.02	< 10	< 10	21	10	100
S 09622	299	238	0.02	12	280	220	5	5	80	0.02	< 10	< 10	22	15	147
S 09623	299	238	0.01	11	340	212	15	5	82	0.02	< 10	< 10	19	10	134
S 09624	299	238	0.01	13	330	58	10	4	80	0.01	< 10	< 10	12	20	350
S 09625	299	238	0.01	10	290	150	15	3	78	0.01	< 10	< 10	13	10	303
S 09626	299	238	0.01	9	90	4940	10	1	52	< 0.01	< 10	< 10	6	5	908
S 09627	299	238	0.01	6	110	3510	20	< 1	40	< 0.01	< 10	< 10	4	15	693
S 09628	299	238	0.01	5	100	2180	30	< 1	39	< 0.01	< 10	< 10	2	5	434
S 09629	299	238	0.01	2	70	3370	35	< 1	43	< 0.01	10	< 10	2	70	567
S 09630	299	238	0.02	8	170	892	10	2	64	0.01	< 10	< 10	9	35	469
S 09631	299	238	0.02	3	330	1765	5	3	56	0.01	< 10	< 10	12	25	688
S 09632	299	238	0.02	7	420	540	10	3	55	0.01	< 10	< 10	12	10	434
S 09633	299	238	0.02	3	250	842	10	2	53	0.01	< 10	< 10	10	5	326
S 09634	299	238	0.02	2	100	5300	15	< 1	48	< 0.01	< 10	< 10	4	15	1540
S 09635	299	238	0.02	6	70	6570	15	< 1	48	< 0.01	< 10	< 10	3	10	1630
S 09636	299	238	0.02	39	270	1360	10	4	78	0.01	< 10	< 10	16	< 5	1115
S 09637	299	238	0.02	6	310	152	10	4	86	0.01	< 10	< 10	16	5	45
S 09638	299	238	0.02	9	360	88	< 5	6	92	0.04	< 10	< 10	30	5	56
S 09639	299	238	0.02	4	270	96	15	5	94	0.03	10	< 10	26	45	69
S 09640	299	238	0.01	7	250	102	10	5	98	0.03	< 10	< 10	22	30	60
S 09641	299	238	0.02	14	250	168	25	5	97	0.02	< 10	< 10	19	20	62
S 09642	299	238	0.02	10	230	68	25	4	109	0.01	< 10	< 10	16	20	38
S 09643	299	238	0.02	14	200	98	15	3	109	0.01	< 10	< 10	15	20	61
S 09644	299	238	0.02	8	170	114	15	3	105	0.01	< 10	< 10	13	10	44
S 09645	299	238	0.02	6	150	94	20	4	108	0.01	< 10	< 10	16	5	38
S 09646	299	238	0.02	7	130	74	20	4	115	0.01	< 10	< 10	14	10	26
S 09647	299	238	0.02	12	150	124	25	5	120	0.02	< 10	< 10	20	< 5	115
S 09648	299	238	0.02	10	100	144	15	4	104	0.02	< 10	< 10	21	< 5	135
S 09649	299	238	0.02	17	190	612	15	4	98	0.02	10	< 10	22	10	8580
S 09650	299	238	0.02	31	160	842	15	4	91	0.02	< 10	< 10	20	5	6630
S 09672	299	238	0.02	11	160	>10000	20	3	100	0.01	< 10	< 10	13	10	>10000
S 09673	299	238	0.02	3	< 10	8460	20	2	112	< 0.01	< 10	< 10	8	< 5	2840
S 09674	299	238	0.02	10	< 10	>10000	15	1	83	< 0.01	10	< 10	5	5	>10000
S 09675	299	238	0.02	5	< 10	>10000	20	1	80	< 0.01	< 10	< 10	5	< 5	5280
S 09676	299	238	0.02	13	< 10	8050	20	1	82	< 0.01	10	< 10	6	< 5	2540
S 09677	299	238	0.02	6	< 10	5390	20	1	82	< 0.01	10	< 10	6	< 5	3360
S 09678	299	238	0.02	10	< 10	3950	20	1	80	< 0.01	10	< 10	6	< 5	2610

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU (BLENDE)
Comments: THESE ARE COMPOSITES

Page : 1
Total Pages: 1
Date : 22-SEP-88
Invoice # : I-8820463
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8820463

SAMPLE DESCRIPTION	PREP CODE		Sn %	Ge %								
S09971-S09975	214	--	< 0.01	0.004								
S09976-S09980	214	--	< 0.01	0.004								
S09981-S09985	214	--	< 0.01	0.005								
S09986-S09990	214	--	< 0.01	0.005								

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 1
Tot. Pages: 4
Date : 25-AUG-88
Invoice # : I-8821112
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821112

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %						
8301	208	--	0.002	0.51	1.12	0.92						
8302	208	--	0.002	0.31	0.54	2.06						
8303	208	--	0.004	0.06	0.13	0.15						
8304	208	--	0.002	0.10	0.16	0.16						
8305	208	--	< 0.002	0.48	1.03	0.82						
8306	208	--	0.002	0.58	1.31	1.04						
8307	208	--	< 0.002	0.64	1.39	0.44						
8308	208	--	< 0.002	1.46	1.66	0.35						
8309	208	--	< 0.002	1.15	2.68	1.43						
8310	208	--	< 0.002	0.22	0.52	0.57						
8311	208	--	< 0.002	0.74	1.34	0.21						
8312	208	--	< 0.002	0.34	0.54	0.61						
8313	208	--	< 0.002	0.23	0.45	0.43						
8314	208	--	< 0.002	0.22	0.46	0.09						
8315	208	--	< 0.002	0.09	0.14	0.69						
8316	208	--	< 0.002	0.03	0.05	0.21						
8317	208	--	< 0.002	0.04	0.07	0.46						
8318	208	--	< 0.002	0.07	0.10	0.48						
8319	208	--	< 0.002	0.12	0.17	0.92						
9776	208	--	< 0.002	0.04	0.02	0.16						
9777	208	--	< 0.002	0.03	0.01	0.08						
9778	208	--	< 0.002	0.06	0.02	0.08						
9779	208	--	0.002	0.03	0.02	0.10						
9780	208	--	< 0.002	0.04	0.02	0.38						
9781	208	--	< 0.002	0.10	0.06	0.85						
9782	208	--	< 0.002	0.34	0.01	0.03						
9783	208	--	< 0.002	0.04	0.01	0.07						
9784	208	--	< 0.002	0.07	0.03	1.02						
9785	208	--	< 0.002	0.09	0.04	0.48						
9786	208	--	< 0.002	0.04	0.01	0.06						
9787	208	--	< 0.002	0.04	0.01	0.03						
9788	208	--	< 0.002	0.06	0.04	0.17						
9789	208	--	< 0.002	0.03	0.01	0.19						
9790	208	--	< 0.002	0.01	< 0.01	0.06						
9791	208	--	< 0.002	0.03	0.01	0.19						
9792	208	--	< 0.002	0.03	< 0.01	0.04						
9793	208	--	< 0.002	< 0.01	0.01	0.04						
9794	208	--	< 0.002	< 0.01	0.01	0.08						
9805	208	--	< 0.002	< 0.01	< 0.01	0.06						
9806	208	--	< 0.002	0.06	0.01	0.59						

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Date : 25-AUG-88
Invoice # : I-8821112
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821112

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
9807	208	--	< 0.002	0.01	0.02	0.14
9808	208	--	< 0.002	0.06	0.02	0.05
9809	208	--	< 0.002	0.03	0.05	0.04
9810	208	--	< 0.002	< 0.01	0.03	0.03
9811	208	--	< 0.002	0.03	0.06	0.04
9812	208	--	< 0.002	0.03	0.02	0.03
9813	208	--	< 0.002	0.10	0.03	0.26
9814	208	--	< 0.002	0.80	1.71	2.37
9815	208	--	< 0.002	7.87	14.30	4.15
9816	208	--	< 0.002	1.84	2.88	2.75
9817	208	--	< 0.002	3.79	9.45	5.49
9818	208	--	< 0.002	0.16	0.33	0.62
9819	208	--	< 0.002	0.10	0.43	1.49
9820	208	--	< 0.002	0.80	2.84	1.26
9821	208	--	< 0.002	10.20	24.6	11.80
9822	208	--	< 0.002	0.99	4.12	0.49
9823	208	--	< 0.002	0.12	0.54	0.34
9824	208	--	< 0.002	0.07	0.27	0.35
9825	208	--	< 0.002	0.06	0.16	0.50
9826	208	--	< 0.002	0.31	0.55	0.85
9827	208	--	< 0.002	0.87	1.60	1.43
9828	208	--	< 0.002	0.92	1.78	1.77
9829	208	--	< 0.002	5.02	8.21	8.67
9830	208	--	< 0.002	2.10	3.92	6.20
9831	208	--	< 0.002	0.45	1.17	1.62
9832	208	--	< 0.002	0.51	1.28	1.26
9833	208	--	< 0.002	0.26	0.62	0.58
9834	208	--	< 0.002	0.22	0.46	0.38
9835	208	--	< 0.002	0.70	1.31	0.19
9836	208	--	< 0.002	0.35	0.77	0.26
9837	208	--	< 0.002	0.16	0.30	0.50
9838	208	--	< 0.002	2.74	4.47	4.41
9839	208	--	< 0.002	3.91	6.23	2.34
9840	208	--	< 0.002	1.92	2.78	3.05
9841	208	--	< 0.002	0.69	0.98	0.48
9842	208	--	< 0.002	0.64	0.90	0.67
9843	208	--	< 0.002	2.33	3.44	1.24
9844	208	--	< 0.002	1.84	3.40	3.97
9845	208	--	< 0.002	0.51	0.99	0.46
9846	208	--	< 0.002	1.25	2.24	0.76

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 3
Total Pages: 4
Date : 25-AUG-88
Invoice # : I-8821112
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821112

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %						
9847	208	--	< 0.002	2.68	8.00	1.76						
9848	208	--	< 0.002	1.84	4.71	1.80						
9849	208	--	< 0.002	0.47	0.91	0.44						
9850	208	--	< 0.002	0.36	1.17	0.85						
9851	208	--	0.002	0.04	0.41	0.16						
9852	208	--	< 0.002	2.54	4.29	2.05						
9853	208	--	< 0.002	3.91	5.26	1.56						
9854	208	--	< 0.002	2.51	3.09	0.98						
9855	208	--	< 0.002	2.22	2.42	1.08						
9856	208	--	< 0.002	2.92	3.14	1.54						
9857	208	--	< 0.002	0.34	0.41	0.32						
9858	208	--	< 0.002	0.10	0.21	0.17						
9859	208	--	< 0.002	0.44	0.66	0.27						
9860	208	--	< 0.002	0.79	1.17	0.55						
9861	208	--	< 0.002	0.47	0.75	0.20						
9862	208	--	0.002	1.20	1.48	0.65						
9863	208	--	< 0.002	0.09	0.17	0.14						
9864	208	--	< 0.002	2.51	2.84	0.44						
9865	208	--	< 0.002	4.61	4.62	1.39						
9866	208	--	< 0.002	3.27	3.08	0.92						
9867	208	--	< 0.002	1.21	1.32	0.30						
9868	208	--	< 0.002	3.67	4.52	0.79						
9869	208	--	< 0.002	12.00	13.40	6.82						
9870	208	--	< 0.002	5.83	13.70	6.71						
9871	208	--	< 0.002	1.46	6.13	3.61						
9872	208	--	< 0.002	0.07	0.14	0.06						
9873	208	--	< 0.002	0.09	0.10	0.07						
9874	208	--	< 0.002	0.23	0.23	0.17						
9875	208	--	< 0.002	0.17	0.19	0.05						
9876	208	--	< 0.002	0.07	0.11	0.03						
9877	208	--	< 0.002	0.06	0.10	0.01						
9878	208	--	< 0.002	0.07	0.13	0.01						
9879	208	--	< 0.002	0.10	0.21	0.02						
9880	208	--	< 0.002	0.13	0.25	0.02						
9881	208	--	< 0.002	0.17	0.22	0.06						
9882	208	--	< 0.002	0.03	0.10	0.02						
9883	208	--	< 0.002	0.15	0.16	0.03						
9884	208	--	< 0.002	0.09	0.20	0.06						
9885	208	--	< 0.002	0.19	0.36	0.11						
9886	208	--	< 0.002	0.73	0.91	0.18						

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 4
Tot. Pages: 4
Date : 25-AUG-88
Invoice # : I-8821112
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821112

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
9887	208	--	< 0.002	50.3	25.8	9.67
9888	208	--	< 0.002	18.30	31.9	9.02
9889	208	--	< 0.002	5.98	7.64	1.52
9890	208	--	< 0.002	5.83	7.79	2.59
9891	208	--	< 0.002	1.37	2.27	0.92
9892	208	--	0.003	4.26	6.14	4.76
9893	208	--	< 0.002	2.25	4.39	3.28
9894	208	--	< 0.002	5.42	9.32	4.56
9895	208	--	< 0.002	2.27	4.56	0.86
9896	208	--	< 0.002	3.32	5.34	2.30
9897	208	--	< 0.002	0.26	0.43	0.13
9898	208	--	< 0.002	0.03	0.06	0.04
9899	208	--	< 0.002	0.26	0.50	0.05
9900	208	--	< 0.002	0.34	1.14	0.85

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Page : 1-A
Tot. Pages: 4
Date : 23-AUG-88
Invoice # : I-8821113
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
8301	299	238	0.16	13.2	20	< 10	< 0.5	< 2	9.27	15.0	12	13	24	1.54	< 10	< 1	0.10	< 10	4.98	974	1
8302	299	238	0.31	6.4	25	10	< 0.5	< 2	8.03	43.0	19	34	27	1.30	< 10	< 1	0.19	< 10	4.43	734	< 1
8303	299	238	0.35	< 0.2	40	10	< 0.5	< 2	12.25	2.0	7	34	16	1.56	< 10	< 1	0.21	< 10	6.70	968	< 1
8304	299	238	0.38	< 0.2	15	10	< 0.5	< 2	11.20	2.5	7	29	24	1.32	< 10	< 1	0.24	< 10	6.18	801	< 1
8305	299	238	0.23	12.4	10	< 10	< 0.5	< 2	11.00	12.5	8	61	22	1.10	< 10	< 1	0.15	< 10	6.12	843	7
8306	299	238	0.06	12.6	5	< 10	< 0.5	< 2	>15.00	17.5	< 1	22	14	1.18	< 10	< 1	0.03	< 10	8.85	1050	< 1
8307	299	238	0.05	13.6	10	< 10	< 0.5	< 2	>15.00	8.0	2	17	14	1.00	< 10	< 1	0.02	< 10	8.79	954	< 1
8308	299	238	0.10	41.4	70	< 10	< 0.5	< 2	12.10	8.5	17	24	127	1.28	< 10	< 1	0.04	< 10	6.71	954	< 1
8309	299	238	0.26	33.6	50	30	< 0.5	< 2	9.19	26.0	22	44	81	1.24	< 10	< 1	0.16	< 10	5.04	821	< 1
8310	299	238	0.20	2.6	10	< 10	< 0.5	< 2	12.50	8.5	4	19	16	1.24	< 10	< 1	0.13	< 10	6.85	1040	< 1
8311	299	238	0.20	19.8	10	< 10	< 0.5	< 2	12.65	3.0	3	21	31	0.91	< 10	< 1	0.15	< 10	6.72	845	< 1
8312	299	238	0.11	6.0	20	< 10	0.5	< 2	13.50	9.5	2	11	65	0.99	< 10	< 1	0.08	< 10	7.04	902	< 1
8313	299	238	0.18	1.8	20	20	< 0.5	< 2	12.60	6.5	4	13	26	0.95	< 10	< 1	0.13	< 10	6.63	793	< 1
8314	299	238	0.15	1.0	15	< 10	< 0.5	< 2	13.85	1.5	2	13	9	0.91	< 10	< 1	0.11	< 10	7.27	882	< 1
8315	299	238	0.20	< 0.2	10	< 10	< 0.5	< 2	13.95	10.5	2	13	12	0.89	< 10	< 1	0.14	< 10	7.40	839	< 1
8316	299	238	0.09	< 0.2	5	< 10	< 0.5	< 2	>15.00	3.0	< 1	16	6	0.81	< 10	< 1	0.07	< 10	8.46	839	< 1
8317	299	238	0.07	< 0.2	5	< 10	< 0.5	< 2	>15.00	7.0	< 1	7	6	0.79	< 10	< 1	0.05	< 10	10.25	904	< 1
8318	299	238	0.10	< 0.2	5	< 10	< 0.5	< 2	>15.00	8.0	< 1	11	9	0.83	< 10	< 1	0.07	< 10	10.10	972	< 1
8319	299	238	0.15	< 0.2	5	< 10	0.5	< 2	>15.00	15.0	< 1	23	29	1.11	< 10	< 1	0.10	< 10	8.65	1195	< 1
9776	299	238	0.09	< 0.2	10	< 10	0.5	< 2	>15.00	2.0	< 1	8	4	1.21	< 10	< 1	0.06	< 10	9.30	1185	1
9777	299	238	0.11	< 0.2	< 5	< 10	0.5	< 2	>15.00	0.5	< 1	11	1	0.93	< 10	< 1	0.09	< 10	9.56	1015	< 1
9778	299	238	0.12	< 0.2	30	60	2.5	< 2	>15.00	0.5	8	33	45	3.00	< 10	1	0.07	< 10	9.00	1155	1
9779	299	238	0.10	< 0.2	< 5	30	1.0	< 2	>15.00	1.5	< 1	10	22	1.03	< 10	< 1	0.07	< 10	10.05	912	1
9780	299	238	0.06	< 0.2	< 5	< 10	0.5	< 2	>15.00	5.0	< 1	11	8	0.89	< 10	< 1	0.04	< 10	10.55	865	< 1
9781	299	238	0.05	< 0.2	15	< 10	1.5	< 2	>15.00	13.0	< 1	22	51	1.69	< 10	< 1	0.02	< 10	9.93	1160	< 1
9782	299	238	0.04	2.2	< 5	< 10	0.5	< 2	>15.00	0.5	< 1	11	39	0.71	< 10	< 1	0.03	< 10	9.86	759	< 1
9783	299	238	0.04	< 0.2	10	< 10	1.5	< 2	>15.00	1.0	< 1	21	4	1.60	< 10	< 1	0.02	< 10	9.75	771	< 1
9784	299	238	0.07	< 0.2	15	< 10	1.5	< 2	>15.00	14.0	< 1	14	13	1.39	< 10	1	0.05	< 10	9.47	865	< 1
9785	299	238	0.12	< 0.2	30	< 10	< 0.5	< 2	>15.00	5.0	< 1	16	14	2.97	< 10	< 1	0.05	< 10	9.86	912	1
9786	299	238	0.05	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	0.5	< 1	12	2	0.94	< 10	< 1	0.03	< 10	10.95	898	< 1
9787	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	9	2	0.86	< 10	< 1	0.01	< 10	11.15	837	< 1
9788	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	2.5	< 1	6	7	0.95	< 10	< 1	0.02	< 10	10.75	885	< 1
9789	299	238	0.03	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	1.5	< 1	9	< 1	0.85	< 10	< 1	0.01	< 10	10.85	804	< 1
9790	299	238	0.02	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	11	< 1	0.92	< 10	< 1	0.02	< 10	10.90	892	< 1
9791	299	238	0.07	< 0.2	5	< 10	< 0.5	< 2	>15.00	2.5	< 1	8	4	1.56	< 10	< 1	0.03	< 10	10.80	1425	< 1
9792	299	238	0.05	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	14	< 1	0.79	< 10	< 1	0.02	< 10	10.70	744	< 1
9793	299	238	0.07	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	4	2	0.92	< 10	< 1	0.04	< 10	10.55	839	< 1
9794	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	1.0	< 1	11	3	0.93	< 10	< 1	0.02	< 10	9.86	876	< 1
9805	299	238	0.20	< 0.2	10	10	< 0.5	< 2	12.50	< 0.5	< 1	14	5	1.35	< 10	< 1	0.13	< 10	6.95	1175	< 1
9806	299	238	0.15	< 0.2	60	10	< 0.5	< 2	12.95	7.0	12	22	26	2.74	< 10	< 1	0.10	< 10	7.05	1410	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Date : 23-AUG-88
Invoice # : I-8821113
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
8301	299	238	0.01	12	330	>10000	15	4	123	< 0.01	< 10	< 10	7	< 5	8370
8302	299	238	0.01	15	370	5390	5	3	100	< 0.01	< 10	< 10	7	< 5	>10000
8303	299	238	0.01	15	240	1260	10	4	143	< 0.01	10	< 10	9	< 5	1420
8304	299	238	0.01	12	270	1485	10	4	155	< 0.01	< 10	< 10	8	< 5	1430
8305	299	238	0.01	9	170	9870	20	2	114	< 0.01	10	< 10	6	< 5	7530
8306	299	238	0.01	5	110	>10000	25	2	106	< 0.01	< 10	< 10	5	< 5	9480
8307	299	238	0.01	7	50	>10000	20	1	102	< 0.01	< 10	< 10	4	< 5	4080
8308	299	238	0.01	15	130	>10000	85	2	103	< 0.01	< 10	< 10	4	< 5	3310
8309	299	238	0.01	18	240	>10000	45	3	90	< 0.01	< 10	< 10	6	< 5	>10000
8310	299	238	0.01	7	160	5190	10	3	129	< 0.01	< 10	< 10	6	< 5	5370
8311	299	238	0.01	5	190	>10000	40	3	127	< 0.01	< 10	< 10	6	< 5	1865
8312	299	238	0.01	7	220	5430	20	3	126	< 0.01	< 10	< 10	5	< 5	5400
8313	299	238	0.01	7	230	4380	10	3	131	< 0.01	< 10	< 10	5	< 5	4020
8314	299	238	0.01	7	130	4430	10	2	136	< 0.01	< 10	< 10	5	< 5	860
8315	299	238	0.01	6	160	1350	5	3	125	< 0.01	< 10	< 10	7	< 5	6160
8316	299	238	0.01	4	130	388	5	2	99	< 0.01	< 10	< 10	5	< 5	1855
8317	299	238	0.02	2	< 10	654	< 5	1	72	< 0.01	< 10	< 10	4	< 5	4170
8318	299	238	0.02	3	30	1020	< 5	2	87	< 0.01	< 10	< 10	4	< 5	4480
8319	299	238	0.01	6	130	1650	5	2	111	< 0.01	< 10	< 10	6	< 5	8050
9776	299	238	0.02	2	< 10	170	5	2	59	< 0.01	< 10	< 10	5	< 5	1385
9777	299	238	0.02	1	< 10	60	< 5	1	50	< 0.01	< 10	< 10	5	< 5	651
9778	299	238	0.02	14	< 10	206	10	2	46	< 0.01	20	10	7	< 5	691
9779	299	238	0.02	2	< 10	186	< 5	1	53	< 0.01	< 10	< 10	4	< 5	870
9780	299	238	0.02	< 1	< 10	200	< 5	1	45	< 0.01	10	10	5	< 5	3290
9781	299	238	0.01	8	< 10	560	10	1	49	< 0.01	10	< 10	5	< 5	7290
9782	299	238	0.02	< 1	< 10	52	40	1	43	< 0.01	< 10	< 10	4	< 5	297
9783	299	238	0.01	4	< 10	86	5	1	39	< 0.01	20	10	5	< 5	581
9784	299	238	0.02	7	20	218	5	1	44	< 0.01	10	< 10	6	< 5	8470
9785	299	238	0.02	9	< 10	310	10	2	46	< 0.01	< 10	< 10	6	< 5	4420
9786	299	238	0.02	1	< 10	58	< 5	1	41	< 0.01	< 10	< 10	3	< 5	556
9787	299	238	0.02	< 1	< 10	52	< 5	1	39	< 0.01	< 10	< 10	3	< 5	315
9788	299	238	0.01	< 1	< 10	308	5	1	47	< 0.01	< 10	< 10	3	< 5	1455
9789	299	238	0.01	1	< 10	48	< 5	1	39	< 0.01	< 10	< 10	3	< 5	1665
9790	299	238	0.01	< 1	< 10	28	< 5	< 1	42	< 0.01	< 10	< 10	3	< 5	538
9791	299	238	0.02	4	< 10	68	5	1	51	< 0.01	< 10	< 10	4	< 5	1620
9792	299	238	0.02	1	< 10	22	< 5	1	43	< 0.01	< 10	< 10	3	< 5	321
9793	299	238	0.01	1	< 10	48	5	1	49	< 0.01	< 10	< 10	3	< 5	313
9794	299	238	0.01	< 1	< 10	52	< 5	1	51	< 0.01	< 10	< 10	3	< 5	702
9805	299	238	0.01	7	120	20	< 5	3	62	< 0.01	< 10	< 10	4	< 5	507
9806	299	238	0.01	26	80	98	10	3	53	< 0.01	20	30	5	< 5	5240

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Date : 23-AUG-88
Invoice # : I-8821113
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
9807	299	238	0.18	< 0.2	25	< 10	< 0.5	< 2	13.60	1.0	1	19	21	1.64	< 10	< 1	0.12	< 10	7.50	1515	1
9808	299	238	0.23	< 0.2	45	10	< 0.5	< 2	>15.00	< 0.5	1	17	17	2.69	< 10	< 1	0.14	< 10	9.23	1665	< 1
9809	299	238	0.07	< 0.2	35	< 10	< 0.5	< 2	>15.00	0.5	2	9	37	3.73	< 10	< 1	0.02	< 10	10.15	1470	1
9810	299	238	0.07	< 0.2	25	< 10	< 0.5	< 2	>15.00	0.5	< 1	11	65	2.55	< 10	< 1	0.03	< 10	10.70	1520	< 1
9811	299	238	0.07	< 0.2	50	< 10	< 0.5	< 2	>15.00	< 0.5	3	19	20	3.64	< 10	< 1	0.03	< 10	10.05	1395	< 1
9812	299	238	0.05	< 0.2	5	< 10	< 0.5	< 2	>15.00	0.5	< 1	9	22	1.94	< 10	< 1	0.02	< 10	10.70	1670	< 1
9813	299	238	0.07	< 0.2	40	< 10	< 0.5	< 2	>15.00	1.0	< 1	15	105	3.47	< 10	< 1	0.02	< 10	10.15	1795	1
9814	299	238	0.18	19.4	35	10	< 0.5	< 2	14.10	31.5	1	25	25	2.72	< 10	2	0.07	< 10	7.84	1090	< 1
9815	299	238	0.39	>200	115	10	< 0.5	4	8.20	50.5	7	25	123	5.62	< 10	< 1	0.16	< 10	4.78	854	< 1
9816	299	238	0.38	53.4	35	10	< 0.5	< 2	11.70	45.5	< 1	18	40	1.70	< 10	< 1	0.20	< 10	6.79	935	4
9817	299	238	0.37	122.5	325	< 10	< 0.5	< 2	5.63	66.0	6	16	138	>15.00	< 10	< 1	0.05	< 10	3.30	687	4
9818	299	238	0.06	< 0.2	10	< 10	< 0.5	< 2	>15.00	11.0	< 1	9	12	1.75	< 10	< 1	0.01	< 10	10.45	1360	< 1
9819	299	238	0.06	< 0.2	< 5	10	< 0.5	< 2	>15.00	45.5	< 1	18	12	1.37	< 10	< 1	< 0.01	< 10	9.61	1770	< 1
9820	299	238	0.06	19.6	10	< 10	< 0.5	< 2	>15.00	27.0	< 1	10	30	0.97	< 10	< 1	0.02	< 10	9.02	859	< 1
9821	299	238	0.13	>200	135	< 10	< 0.5	26	6.34	76.5	13	23	513	3.31	< 10	< 1	0.01	< 10	3.68	1020	< 1
9822	299	238	0.07	23.0	25	< 10	< 0.5	< 2	>15.00	9.5	< 1	4	39	1.09	< 10	< 1	0.04	< 10	9.94	715	< 1
9823	299	238	0.08	< 0.2	5	< 10	< 0.5	< 2	>15.00	8.5	< 1	11	10	0.84	< 10	< 1	0.05	< 10	10.05	681	< 1
9824	299	238	0.06	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	5.5	< 1	9	5	0.71	< 10	< 1	0.04	< 10	10.35	659	< 1
9825	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	>15.00	8.0	< 1	12	10	0.78	< 10	< 1	0.03	< 10	9.66	718	< 1
9826	299	238	0.05	2.2	< 5	< 10	< 0.5	< 2	>15.00	16.0	< 1	6	7	0.63	< 10	< 1	0.03	< 10	9.31	576	< 1
9827	299	238	0.06	21.2	5	< 10	< 0.5	< 2	>15.00	26.5	< 1	7	15	0.80	< 10	< 1	0.04	< 10	9.13	610	< 1
9828	299	238	0.07	23.6	5	< 10	< 0.5	< 2	>15.00	35.0	< 1	8	15	0.95	< 10	< 1	0.04	< 10	10.05	777	1
9829	299	238	0.20	162.5	55	< 10	< 0.5	18	5.58	>99.9	18	12	166	1.39	< 10	< 1	0.12	10	3.30	658	< 1
9830	299	238	0.16	63.4	30	< 10	< 0.5	< 2	11.35	>99.9	6	8	66	1.44	< 10	< 1	0.09	< 10	6.51	1135	< 1
9831	299	238	0.16	10.0	30	10	< 0.5	< 2	12.45	28.5	2	16	19	1.43	< 10	< 1	0.10	< 10	7.27	1325	1
9832	299	238	0.15	10.6	30	< 10	< 0.5	< 2	13.10	20.5	< 1	15	24	1.21	< 10	< 1	0.08	< 10	7.73	761	1
9833	299	238	0.15	3.0	25	< 10	< 0.5	< 2	11.95	11.0	< 1	9	8	0.97	< 10	< 1	0.09	< 10	7.00	650	< 1
9834	299	238	0.13	0.6	15	< 10	< 0.5	< 2	13.35	8.0	< 1	6	5	0.85	< 10	< 1	0.08	< 10	7.83	569	< 1
9835	299	238	0.09	15.0	5	< 10	< 0.5	< 2	>15.00	5.0	< 1	11	8	0.83	< 10	< 1	0.06	< 10	9.85	649	< 1
9836	299	238	0.10	3.6	< 5	< 10	< 0.5	< 2	>15.00	5.0	< 1	7	3	0.72	< 10	< 1	0.05	< 10	10.35	560	< 1
9837	299	238	0.10	< 0.2	10	< 10	< 0.5	< 2	>15.00	8.5	< 1	13	4	0.83	< 10	1	0.07	< 10	10.00	653	1
9838	299	238	0.06	80.2	40	< 10	< 0.5	< 2	11.55	88.5	2	16	71	1.49	< 10	< 1	0.02	< 10	6.94	798	< 1
9839	299	238	0.10	125.0	45	< 10	< 0.5	< 2	10.20	41.0	3	9	35	0.94	< 10	< 1	0.06	< 10	6.08	592	< 1
9840	299	238	0.10	56.2	40	30	< 0.5	< 2	10.70	63.0	3	16	20	0.97	< 10	1	0.07	< 10	6.38	539	1
9841	299	238	0.07	15.0	5	< 10	< 0.5	< 2	14.90	8.5	< 1	7	3	0.77	< 10	< 1	0.04	< 10	8.94	561	< 1
9842	299	238	0.21	15.0	20	< 10	< 0.5	< 2	12.20	11.0	< 1	9	7	0.71	< 10	< 1	0.14	< 10	7.35	479	1
9843	299	238	0.16	70.6	70	< 10	< 0.5	< 2	10.80	21.0	2	6	17	0.87	< 10	< 1	0.10	< 10	6.48	483	< 1
9844	299	238	0.09	53.0	30	< 10	< 0.5	< 2	13.40	65.0	< 1	6	71	1.39	< 10	< 1	0.05	< 10	8.10	1020	3
9845	299	238	0.06	8.8	10	10	< 0.5	< 2	>15.00	7.0	< 1	6	6	0.72	< 10	< 1	0.04	< 10	9.50	537	< 1
9846	299	238	0.10	33.8	20	< 10	< 0.5	< 2	14.05	13.0	< 1	7	24	0.81	< 10	< 1	0.07	< 10	8.44	600	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
9807	299	238	0.01	9	50	64	5	3	62	< 0.01	10	10	4	< 5	1265
9808	299	238	0.02	16	< 10	98	5	2	57	< 0.01	< 10	10	5	< 5	490
9809	299	238	0.02	13	< 10	316	5	1	51	< 0.01	< 10	20	6	< 5	392
9810	299	238	0.02	9	< 10	192	5	1	62	< 0.01	< 10	20	5	< 5	242
9811	299	238	0.02	17	< 10	486	5	1	50	< 0.01	20	40	6	< 5	381
9812	299	238	0.02	6	< 10	98	5	1	84	< 0.01	< 10	20	4	< 5	253
9813	299	238	0.02	13	< 10	210	5	1	58	< 0.01	< 10	< 10	7	< 5	2280
9814	299	238	0.01	14	130	>10000	35	1	30	< 0.01	< 10	< 10	6	< 5	>10000
9815	299	238	0.01	17	210	>10000	240	3	23	< 0.01	10	10	10	< 5	>10000
9816	299	238	0.02	7	180	>10000	80	3	29	< 0.01	< 10	< 10	7	< 5	>10000
9817	299	238	0.01	16	160	>10000	285	2	15	< 0.01	60	90	20	< 5	>10000
9818	299	238	0.02	5	< 10	2960	10	1	28	< 0.01	< 10	10	4	< 5	5110
9819	299	238	0.02	9	< 10	3760	10	1	18	< 0.01	< 10	< 10	4	< 5	>10000
9820	299	238	0.01	2	80	>10000	25	1	27	< 0.01	< 10	< 10	4	< 5	>10000
9821	299	238	0.01	12	370	>10000	635	1	14	< 0.01	< 10	< 10	6	< 5	>10000
9822	299	238	0.02	3	< 10	>10000	110	1	18	< 0.01	< 10	< 10	4	< 5	4300
9823	299	238	0.02	2	< 10	5180	15	1	20	< 0.01	< 10	20	4	< 5	2990
9824	299	238	0.02	< 1	< 10	2430	5	1	18	< 0.01	< 10	< 10	3	< 5	3150
9825	299	238	0.01	1	< 10	1380	5	1	16	< 0.01	< 10	20	4	< 5	4350
9826	299	238	0.01	2	< 10	5060	10	1	15	< 0.01	< 10	< 10	3	< 5	7570
9827	299	238	0.01	3	10	>10000	45	1	15	< 0.01	< 10	< 10	3	< 5	>10000
9828	299	238	0.02	5	20	>10000	80	1	14	< 0.01	< 10	10	3	< 5	>10000
9829	299	238	0.01	22	510	>10000	340	3	11	< 0.01	< 10	< 10	6	< 5	>10000
9830	299	238	0.01	10	330	>10000	95	2	19	< 0.01	< 10	< 10	6	< 5	>10000
9831	299	238	0.01	9	200	>10000	35	2	21	< 0.01	< 10	10	5	< 5	>10000
9832	299	238	0.01	5	120	>10000	35	2	21	< 0.01	< 10	< 10	4	< 5	>10000
9833	299	238	0.01	7	110	5820	15	2	22	< 0.01	< 10	< 10	3	< 5	5040
9834	299	238	0.01	4	50	4030	15	2	23	< 0.01	< 10	< 10	3	< 5	3340
9835	299	238	0.01	3	< 10	>10000	35	1	20	< 0.01	< 10	< 10	3	< 5	1725
9836	299	238	0.02	1	< 10	7100	15	1	19	< 0.01	< 10	< 10	3	< 5	2200
9837	299	238	0.02	3	< 10	2690	20	1	19	< 0.01	< 10	< 10	3	< 5	4370
9838	299	238	0.01	10	180	>10000	370	1	20	< 0.01	< 10	< 10	3	< 5	>10000
9839	299	238	0.01	7	210	>10000	305	2	19	< 0.01	< 10	< 10	3	< 5	>10000
9840	299	238	0.01	6	220	>10000	200	2	16	< 0.01	< 10	< 10	4	< 5	>10000
9841	299	238	0.01	2	30	8490	45	1	17	< 0.01	< 10	< 10	4	< 5	3870
9842	299	238	0.01	6	100	8160	45	2	21	< 0.01	< 10	< 10	4	< 5	5540
9843	299	238	0.01	11	130	>10000	240	2	20	< 0.01	< 10	< 10	3	< 5	>10000
9844	299	238	0.01	7	120	>10000	165	1	18	< 0.01	< 10	< 10	3	< 5	>10000
9845	299	238	0.01	4	< 10	8640	30	1	20	< 0.01	< 10	< 10	2	< 5	3660
9846	299	238	0.01	4	40	>10000	60	1	27	< 0.01	< 10	< 10	3	< 5	6120

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU(BLENDE)
Comments:

Date : 23-AUG-88
Invoice # : I-8821113
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
9847	299 238	0.05	81.2	60	< 10	< 0.5	< 2	11.70	31.5	< 1	19	15	0.99	< 10	< 1	0.02	< 10	6.93	769	1
9848	299 238	0.04	53.4	30	10	< 0.5	< 2	12.60	32.0	< 1	11	11	0.79	< 10	< 1	0.01	< 10	7.55	623	< 1
9849	299 238	0.04	6.8	10	10	< 0.5	< 2	14.10	6.5	< 1	7	82	1.41	< 10	< 1	0.01	< 10	8.23	1460	< 1
9850	299 238	0.07	5.2	15	< 10	< 0.5	< 2	14.50	13.0	< 1	12	38	1.00	< 10	< 1	0.04	< 10	9.26	900	1
9851	299 238	0.02	< 0.2	5	< 10	< 0.5	< 2	13.10	2.5	< 1	16	2	0.80	< 10	< 1	< 0.01	< 10	8.51	556	1
9852	299 238	0.03	75.0	5	< 10	< 0.5	< 2	12.30	36.5	< 1	16	43	0.82	< 10	< 1	0.01	< 10	7.82	744	< 1
9853	299 238	0.04	111.5	15	< 10	< 0.5	< 2	13.50	27.0	< 1	9	65	0.77	< 10	< 1	0.02	< 10	8.57	601	< 1
9854	299 238	0.06	72.4	20	< 10	< 0.5	< 2	12.10	16.0	< 1	14	20	0.70	< 10	< 1	0.03	< 10	7.73	531	1
9855	299 238	0.06	63.4	25	< 10	< 0.5	< 2	12.60	16.5	< 1	7	17	0.69	< 10	< 1	0.04	< 10	7.93	501	< 1
9856	299 238	0.07	81.2	20	< 10	< 0.5	< 2	11.95	25.5	< 1	8	27	0.81	< 10	< 1	0.04	< 10	7.58	493	1
9857	299 238	0.08	5.0	5	< 10	< 0.5	< 2	13.60	5.0	< 1	7	7	0.61	< 10	< 1	0.05	< 10	8.69	443	< 1
9858	299 238	0.08	< 0.2	5	< 10	< 0.5	< 2	13.75	2.5	< 1	5	2	0.72	< 10	< 1	0.06	< 10	8.80	623	< 1
9859	299 238	0.06	8.0	5	< 10	< 0.5	< 2	12.95	3.5	< 1	6	11	0.64	< 10	< 1	0.04	< 10	7.76	514	< 1
9860	299 238	0.06	16.6	10	< 10	< 0.5	< 2	14.65	8.5	< 1	5	12	0.64	< 10	< 1	0.04	< 10	8.83	476	< 1
9861	299 238	0.07	7.4	< 5	< 10	< 0.5	< 2	>15.00	3.5	< 1	2	2	0.64	< 10	< 1	0.05	< 10	9.54	496	< 1
9862	299 238	0.05	28.6	< 5	< 10	< 0.5	< 2	>15.00	10.5	< 1	6	17	0.75	< 10	< 1	0.04	< 10	9.68	595	< 1
9863	299 238	0.05	< 0.2	< 5	10	< 0.5	< 2	>15.00	2.5	< 1	4	2	0.76	< 10	< 1	0.03	< 10	10.00	579	< 1
9864	299 238	0.12	71.8	35	< 10	< 0.5	< 2	11.70	8.0	2	5	11	0.98	< 10	< 1	0.09	< 10	6.98	520	1
9865	299 238	0.04	135.5	15	< 10	< 0.5	< 2	>15.00	24.0	< 1	6	34	0.84	< 10	< 1	0.03	< 10	9.34	544	1
9866	299 238	0.02	91.2	< 5	< 10	< 0.5	< 2	>15.00	16.0	< 1	2	20	0.81	< 10	< 1	0.01	< 10	9.77	589	< 1
9867	299 238	0.08	32.6	30	< 10	0.5	< 2	13.75	5.5	< 1	2	9	0.84	< 10	< 1	0.05	< 10	9.29	520	< 1
9868	299 238	0.15	112.0	40	< 10	0.5	< 2	8.50	14.5	8	11	40	1.13	< 10	< 1	0.10	< 10	5.55	538	< 1
9869	299 238	0.09	>200	50	< 10	< 0.5	12	6.78	>99.9	11	13	193	1.32	10	< 1	0.06	10	4.26	535	1
9870	299 238	0.05	160.0	45	< 10	< 0.5	< 2	10.20	>99.9	9	9	181	1.63	< 10	< 1	0.03	< 10	6.35	1110	3
9871	299 238	0.15	38.4	45	< 10	0.5	6	7.81	58.5	15	8	60	1.74	10	< 1	0.10	10	4.65	1110	< 1
9872	299 238	0.27	< 0.2	25	< 10	0.5	< 2	7.45	1.0	11	8	6	1.26	< 10	< 1	0.17	10	4.82	656	< 1
9873	299 238	0.14	< 0.2	65	10	0.5	< 2	8.40	0.5	32	5	13	1.18	< 10	< 1	0.08	10	5.46	577	1
9874	299 238	0.13	3.4	55	< 10	0.5	< 2	9.53	3.5	16	5	37	1.39	< 10	< 1	0.08	< 10	6.21	621	1
9875	299 238	0.16	2.2	15	< 10	< 0.5	< 2	8.37	0.5	10	4	20	1.00	< 10	< 1	0.10	10	5.43	532	< 1
9876	299 238	0.18	< 0.2	5	< 10	0.5	< 2	7.81	0.5	11	1	8	1.06	< 10	< 1	0.12	10	5.02	556	< 1
9877	299 238	0.34	0.6	25	10	< 0.5	< 2	7.06	< 0.5	14	3	8	1.22	< 10	< 1	0.24	< 10	4.27	454	< 1
9878	299 238	0.37	0.4	15	10	0.5	< 2	7.77	< 0.5	7	2	10	1.01	< 10	< 1	0.27	< 10	4.71	461	< 1
9879	299 238	0.21	1.6	10	10	< 0.5	< 2	7.12	< 0.5	5	< 1	15	0.90	< 10	< 1	0.16	< 10	4.30	439	1
9880	299 238	0.22	3.2	25	10	0.5	< 2	6.43	< 0.5	8	< 1	16	1.03	< 10	< 1	0.16	< 10	3.85	385	1
9881	299 238	0.17	1.6	35	< 10	< 0.5	< 2	11.00	0.5	15	2	15	1.04	< 10	< 1	0.12	< 10	6.68	608	1
9882	299 238	0.19	< 0.2	20	20	< 0.5	< 2	9.56	< 0.5	4	2	11	1.03	< 10	< 1	0.14	< 10	5.85	563	< 1
9883	299 238	0.11	0.4	35	< 10	< 0.5	< 2	12.05	< 0.5	9	< 1	26	1.05	< 10	< 1	0.07	< 10	7.35	670	1
9884	299 238	0.26	1.0	10	10	< 0.5	< 2	8.35	1.0	5	2	8	1.07	< 10	< 1	0.18	< 10	5.08	502	< 1
9885	299 238	0.28	5.4	30	10	< 0.5	< 2	5.56	2.0	12	2	14	0.82	< 10	< 1	0.20	< 10	3.41	402	< 1
9886	299 238	0.14	19.8	25	< 10	< 0.5	< 2	9.46	2.5	9	3	51	1.06	< 10	< 1	0.09	< 10	5.81	625	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Date :23-AUG-88
Invoice # :I-8821113
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
9847	299	238	0.01	6	50	>10000	120	1	18	< 0.01	< 10	< 10	3	< 5	>10000
9848	299	238	0.01	3	30	>10000	70	1	18	< 0.01	< 10	< 10	2	< 5	>10000
9849	299	238	0.01	4	< 10	7360	60	1	37	< 0.01	< 10	< 10	2	< 5	3250
9850	299	238	0.01	2	< 10	9730	45	1	25	< 0.01	< 10	< 10	3	< 5	7220
9851	299	238	0.01	2	< 10	3500	25	< 1	14	< 0.01	< 10	< 10	3	< 5	1355
9852	299	238	0.01	4	20	>10000	125	< 1	21	< 0.01	< 10	< 10	3	< 5	>10000
9853	299	238	0.01	3	30	>10000	320	1	20	< 0.01	< 10	< 10	4	< 5	>10000
9854	299	238	0.01	3	30	>10000	265	1	27	< 0.01	< 10	< 10	3	< 5	8160
9855	299	238	0.01	4	30	>10000	105	1	30	< 0.01	< 10	< 10	2	< 5	8630
9856	299	238	0.01	3	50	>10000	250	1	33	< 0.01	< 10	< 10	2	< 5	>10000
9857	299	238	0.01	< 1	< 10	3590	15	2	28	< 0.01	< 10	< 10	3	< 5	2710
9858	299	238	0.01	1	< 10	1730	10	1	30	< 0.01	< 10	< 10	2	< 5	1430
9859	299	238	0.01	2	< 10	5530	15	1	32	< 0.01	< 10	< 10	2	< 5	1940
9860	299	238	0.01	< 1	< 10	9290	25	1	26	< 0.01	< 10	< 10	3	< 5	4120
9861	299	238	0.01	1	< 10	6260	15	1	23	< 0.01	< 10	< 10	2	< 5	1475
9862	299	238	0.01	< 1	< 10	>10000	35	1	23	< 0.01	< 10	< 10	2	< 5	4870
9863	299	238	0.02	1	< 10	1365	5	1	31	< 0.01	< 10	< 10	3	< 5	1090
9864	299	238	0.01	9	110	>10000	70	3	32	< 0.01	< 10	< 10	3	< 5	3510
9865	299	238	0.02	4	< 10	>10000	245	1	20	< 0.01	< 10	< 10	2	< 5	9940
9866	299	238	0.02	< 1	< 10	>10000	160	< 1	23	< 0.01	< 10	< 10	2	< 5	6890
9867	299	238	0.01	5	30	>10000	60	2	27	< 0.01	< 10	< 10	4	< 5	2810
9868	299	238	0.01	14	220	>10000	150	3	28	< 0.01	< 10	< 10	5	< 5	7650
9869	299	238	0.01	12	250	>10000	1125	2	18	< 0.01	10	40	3	< 5	>10000
9870	299	238	0.01	15	150	>10000	275	1	28	< 0.01	< 10	50	2	< 5	>10000
9871	299	238	0.01	20	260	>10000	55	3	49	< 0.01	< 10	20	4	< 5	>10000
9872	299	238	0.01	28	220	910	5	3	48	< 0.01	< 10	< 10	5	< 5	481
9873	299	238	0.01	34	220	710	10	3	47	< 0.01	< 10	< 10	6	< 5	572
9874	299	238	0.01	14	180	1680	25	3	51	< 0.01	< 10	< 10	5	< 5	1415
9875	299	238	0.01	10	240	1360	10	3	48	< 0.01	< 10	< 10	5	< 5	449
9876	299	238	0.01	12	270	794	5	3	49	< 0.01	< 10	< 10	4	< 5	319
9877	299	238	0.01	22	460	900	5	4	50	< 0.01	< 10	< 10	5	< 5	145
9878	299	238	0.01	10	420	1150	5	5	56	< 0.01	< 10	< 10	6	< 5	97
9879	299	238	0.01	5	430	1725	5	4	54	< 0.01	< 10	< 10	3	< 5	140
9880	299	238	0.01	10	460	2120	10	4	48	< 0.01	< 10	< 10	3	< 5	187
9881	299	238	0.01	11	320	1885	10	3	60	< 0.01	< 10	< 10	5	< 5	566
9882	299	238	0.01	7	330	800	5	4	60	< 0.01	< 10	< 10	4	< 5	157
9883	299	238	0.01	10	200	1360	15	3	63	< 0.01	< 10	< 10	4	< 5	298
9884	299	238	0.01	6	380	1710	10	4	52	< 0.01	< 10	< 10	4	< 5	539
9885	299	238	0.01	10	310	3070	15	3	38	< 0.01	< 10	< 10	4	< 5	1015
9886	299	238	0.01	12	170	7910	145	3	52	< 0.01	< 10	< 10	3	< 5	1560

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Date :23-AUG-88
Invoice # :I-8821113
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
9887	299	238	0.06	>200	60	< 10	< 0.5	< 2	3.43	>99.9	38	19	3820	0.99	< 10	< 1	0.03	< 10	1.98	312	2
9888	299	238	0.04	>200	110	< 10	< 0.5	22	2.10	>99.9	59	19	264	0.98	10	< 1	0.03	< 10	1.08	165	< 1
9889	299	238	0.05	166.0	45	< 10	< 0.5	< 2	8.08	22.0	23	16	94	1.00	< 10	< 1	0.03	< 10	4.85	603	< 1
9890	299	238	0.03	159.0	10	< 10	< 0.5	< 2	9.66	40.0	3	15	51	0.72	< 10	< 1	0.01	< 10	5.91	621	< 1
9891	299	238	0.04	36.4	< 5	< 10	< 0.5	< 2	11.80	15.5	< 1	16	13	0.72	< 10	< 1	0.02	< 10	7.29	662	< 1
9892	299	238	0.04	121.0	30	< 10	< 0.5	< 2	10.15	76.5	14	14	54	0.82	< 10	< 1	0.01	< 10	6.11	581	3
9893	299	238	0.07	63.8	5	< 10	< 0.5	< 2	9.93	54.5	10	19	40	0.85	< 10	< 1	0.04	< 10	6.02	670	< 1
9894	299	238	0.07	146.0	230	< 10	< 0.5	< 2	8.80	72.0	87	13	68	0.86	< 10	< 1	0.05	< 10	5.14	551	< 1
9895	299	238	0.22	65.2	305	< 10	< 0.5	< 2	6.53	12.0	162	27	62	0.86	< 10	< 1	0.15	< 10	4.00	537	< 1
9896	299	238	0.06	97.0	50	< 10	< 0.5	< 2	12.30	36.0	16	16	47	0.85	< 10	< 1	0.04	< 10	7.58	702	< 1
9897	299	238	0.28	4.0	40	< 10	< 0.5	< 2	11.35	2.5	6	18	6	1.11	< 10	< 1	0.20	< 10	6.96	810	< 1
9898	299	238	0.23	< 0.2	5	10	< 0.5	< 2	10.10	0.5	< 1	14	1	1.20	< 10	< 1	0.17	< 10	6.10	842	< 1
9899	299	238	0.41	5.0	10	10	< 0.5	< 2	10.25	1.0	< 1	14	5	1.17	< 10	< 1	0.29	< 10	6.25	745	< 1
9900	299	238	0.21	6.6	25	< 10	< 0.5	< 2	10.65	14.0	6	11	23	1.57	< 10	< 1	0.15	< 10	6.33	1075	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T \CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Date : 23-AUG-88
Invoice # : I-8821113
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821113

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
9887	299	238	0.01	26	340	>10000	4540	1	20	< 0.01	< 10	< 10	2	< 5	>10000
9888	299	238	0.01	35	330	>10000	620	< 1	10	< 0.01	< 10	< 10	< 1	< 5	>10000
9889	299	238	0.01	19	160	>10000	225	1	40	< 0.01	< 10	< 10	2	< 5	>10000
9890	299	238	0.01	5	130	>10000	200	1	45	< 0.01	< 10	< 10	1	< 5	>10000
9891	299	238	0.01	5	100	>10000	50	1	67	< 0.01	< 10	< 10	2	< 5	7640
9892	299	238	0.01	11	170	>10000	145	1	55	< 0.01	< 10	< 10	1	< 5	>10000
9893	299	238	0.01	10	250	>10000	70	2	78	< 0.01	< 10	< 10	2	< 5	>10000
9894	299	238	0.01	53	450	>10000	155	2	53	< 0.01	< 10	10	3	< 5	>10000
9895	299	238	0.01	75	540	>10000	75	2	65	< 0.01	< 10	< 10	6	< 5	7630
9896	299	238	0.01	16	130	>10000	115	1	52	< 0.01	< 10	< 10	2	< 5	>10000
9897	299	238	0.01	14	160	3490	25	3	98	< 0.01	< 10	< 10	5	< 5	1130
9898	299	238	0.01	7	280	504	< 5	4	146	< 0.01	< 10	< 10	5	< 5	417
9899	299	238	0.01	8	320	4230	5	4	139	< 0.01	< 10	< 10	8	< 5	474
9900	299	238	0.01	10	270	9550	10	4	133	< 0.01	< 10	< 10	7	< 5	7400

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU(BLENDE)
Comments:

Page : 1
Tot. Pages: 1
Date : 20-AUG-88
Invoice # : I-8821211
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821211

SAMPLE DESCRIPTION	PREP CODE		Au oz/T RUSH	Ag oz/T RUSH	Pb %	Zn %						
S 09679	258	--	< 0.002	0.15	0.46	0.24						
S 09680	258	--	< 0.002	0.83	1.66	0.72						
S 09681	258	--	< 0.002	0.12	0.14	0.05						
S 09682	258	--	< 0.002	0.09	0.24	0.08						
S 09683	258	--	< 0.002	0.31	1.28	1.15						
S 09684	258	--	< 0.002	0.20	0.79	0.74						
S 09685	258	--	< 0.002	0.12	0.48	0.21						
S 09690	258	--	< 0.002	0.31	0.90	1.59						
S 09691	258	--	< 0.002	0.06	0.16	0.17						
S 09692	258	--	< 0.002	0.04	0.06	0.05						
S 09693	258	--	< 0.002	0.02	0.05	0.03						
S 09694	258	--	< 0.002	0.03	0.08	0.23						
S 09695	258	--	< 0.002	0.07	0.16	0.37						
S 09696	258	--	< 0.002	0.09	0.13	0.06						
S 09697	258	--	< 0.002	0.04	0.10	0.03						
S 09751	258	--	< 0.002	0.03	0.06	0.02						
S 09752	258	--	< 0.002	< 0.01	0.05	0.02						
S 09753	258	--	< 0.002	0.06	0.09	0.03						
S 09754	258	--	< 0.002	0.10	0.23	0.27						
S 09755	258	--	< 0.002	0.39	1.17	0.21						
S 09756	258	--	< 0.002	0.82	1.60	0.20						
S 09757	258	--	< 0.002	0.32	0.91	0.74						
S 09758	258	--	< 0.002	1.08	0.52	0.33						
S 09759	258	--	< 0.002	0.19	1.20	0.41						
S 09760	258	--	< 0.002	0.27	1.14	0.59						
S 09761	258	--	< 0.002	0.98	3.32	1.22						
S 09762	258	--	< 0.002	0.83	3.14	0.72						
S 09763	258	--	< 0.002	0.08	0.31	0.13						
S 09764	258	--	< 0.002	0.06	0.27	0.11						
S 09765	258	--	< 0.002	0.04	0.23	0.04						
S 09766	258	--	< 0.002	0.66	1.51	2.70						
S 09767	258	--	< 0.002	0.54	0.93	1.13						
S 09768	258	--	< 0.002	0.58	0.77	0.79						
S 09769	258	--	0.002	0.23	0.41	0.69						
S 09770	258	--	< 0.002	0.98	1.87	2.06						
S 09771	258	--	< 0.002	2.73	3.44	3.65						
S 09772	258	--	< 0.002	1.90	2.42	2.22						
S 09773	258	--	< 0.002	0.09	0.06	0.57						
S 09774	258	--	< 0.002	0.39	0.08	2.06						
S 09775	258	--	< 0.002	0.45	0.13	2.70						

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T: CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU BLENDE
Comments:

Date : 23-AUG-88
Invoice # : I-8821212
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821212

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 09679	299	238	0.07	2.6	< 5	< 10	< 0.5	< 2	12.80	3.5	2	20	18	0.68	20	< 1	0.06	< 10	8.66	668	< 1
S 09680	299	238	0.02	25.0	< 5	< 10	< 0.5	< 2	12.40	11.0	3	13	139	0.67	20	< 1	0.02	< 10	8.40	654	1
S 09681	299	238	0.03	1.6	< 5	< 10	< 0.5	< 2	12.40	0.5	3	17	33	0.65	20	< 1	0.03	< 10	8.43	623	1
S 09682	299	238	0.10	1.0	10	< 10	< 0.5	< 2	12.90	1.0	5	9	16	0.90	20	< 1	0.09	< 10	8.56	737	1
S 09683	299	238	0.08	8.0	15	< 10	< 0.5	< 2	11.80	16.5	8	10	29	0.99	20	< 1	0.07	< 10	7.84	702	1
S 09684	299	238	0.02	3.6	< 5	< 10	< 0.5	< 2	14.35	11.0	6	14	13	0.85	20	< 1	0.02	< 10	9.63	741	1
S 09685	299	238	0.09	2.4	5	< 10	< 0.5	< 2	10.70	3.0	7	9	12	0.84	10	< 1	0.09	< 10	7.11	558	1
S 09690	299	238	0.06	7.6	10	< 10	< 0.5	< 2	11.35	23.5	11	10	63	0.86	10	< 1	0.06	< 10	7.56	571	1
S 09691	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	14.45	2.5	3	14	2	0.68	20	< 1	0.04	< 10	9.72	659	< 1
S 09692	299	238	0.27	< 0.2	5	10	< 0.5	< 2	10.80	0.5	11	10	20	1.01	10	< 1	0.25	< 10	7.13	576	1
S 09693	299	238	0.27	< 0.2	< 5	10	< 0.5	< 2	9.21	0.5	6	10	12	0.89	10	< 1	0.26	< 10	5.95	532	< 1
S 09694	299	238	0.28	< 0.2	5	< 10	< 0.5	< 2	9.10	3.5	9	12	11	0.86	10	< 1	0.26	< 10	5.91	536	< 1
S 09695	299	238	0.13	0.2	< 5	< 10	< 0.5	< 2	11.70	5.5	5	8	9	0.72	10	< 1	0.13	< 10	7.73	565	< 1
S 09696	299	238	0.09	0.4	10	< 10	< 0.5	< 2	11.90	1.0	5	8	15	0.72	10	< 1	0.08	< 10	7.87	578	1
S 09697	299	238	0.04	< 0.2	< 5	< 10	< 0.5	< 2	14.15	0.5	6	4	6	0.75	20	< 1	0.03	< 10	9.34	651	1
S 09751	299	238	0.13	< 0.2	15	< 10	< 0.5	< 2	10.45	< 0.5	12	6	19	1.03	10	< 1	0.12	< 10	6.81	530	< 1
S 09752	299	238	0.14	< 0.2	5	< 10	< 0.5	< 2	10.85	< 0.5	7	5	14	0.82	10	< 1	0.13	< 10	7.02	525	< 1
S 09753	299	238	0.31	0.4	10	10	< 0.5	< 2	9.31	< 0.5	9	10	13	0.75	10	< 1	0.27	< 10	6.05	477	< 1
S 09754	299	238	0.15	1.8	15	< 10	< 0.5	< 2	11.20	4.0	10	10	23	0.89	10	< 1	0.13	< 10	7.36	641	< 1
S 09755	299	238	0.03	9.6	10	< 10	< 0.5	< 2	12.85	3.5	11	11	81	1.08	10	< 1	0.02	< 10	8.26	817	4
S 09756	299	238	0.12	24.8	85	< 10	< 0.5	< 2	11.85	3.5	29	16	389	1.56	10	< 1	0.10	< 10	7.56	938	< 1
S 09757	299	238	0.08	9.2	60	< 10	< 0.5	< 2	12.15	11.0	23	12	127	2.04	20	< 1	0.06	< 10	7.47	1490	< 1
S 09758	299	238	0.08	33.2	20	< 10	< 0.5	< 2	11.95	5.0	13	9	423	1.36	20	< 1	0.05	< 10	7.52	1310	1
S 09759	299	238	0.34	4.8	15	10	< 0.5	< 2	12.35	7.5	11	25	37	3.01	20	< 1	0.17	< 10	6.88	2780	< 1
S 09760	299	238	0.21	6.2	30	10	< 0.5	< 2	14.20	8.5	10	20	45	2.81	20	< 1	0.08	< 10	8.26	2440	1
S 09761	299	238	0.04	27.4	110	< 10	< 0.5	< 2	12.35	17.0	8	9	28	4.03	20	< 1	0.02	< 10	7.82	1100	< 1
S 09762	299	238	0.04	23.0	70	< 10	< 0.5	< 2	13.30	9.5	9	8	27	3.36	20	< 1	0.02	< 10	8.47	1115	< 1
S 09763	299	238	0.12	1.2	10	< 10	< 0.5	< 2	10.85	1.5	3	16	5	1.27	10	< 1	0.10	< 10	6.90	1015	< 1
S 09764	299	238	0.26	0.4	10	< 10	< 0.5	< 2	10.55	1.5	5	17	9	1.56	10	< 1	0.20	< 10	7.09	1170	< 1
S 09765	299	238	0.12	< 0.2	15	< 10	< 0.5	< 2	11.10	0.5	5	10	5	1.26	10	< 1	0.09	< 10	7.54	1005	< 1
S 09766	299	238	0.08	17.8	65	< 10	< 0.5	< 2	10.25	28.5	12	57	23	1.73	10	< 1	0.06	< 10	7.00	860	< 1
S 09767	299	238	0.07	14.2	100	< 10	< 0.5	< 2	12.20	13.0	9	14	24	3.58	10	< 1	0.05	< 10	8.29	1065	< 1
S 09768	299	238	0.19	14.6	225	20	< 0.5	< 2	7.72	8.0	44	25	38	6.00	10	< 1	0.14	< 10	5.14	931	3
S 09769	299	238	0.17	6.0	55	< 10	< 0.5	< 2	10.80	8.5	9	9	27	2.10	10	< 1	0.12	< 10	7.33	937	3
S 09770	299	238	0.25	30.0	130	< 10	< 0.5	< 2	9.65	23.5	19	31	27	4.37	10	< 1	0.18	< 10	6.44	1030	2
S 09771	299	238	0.11	80.4	340	< 10	< 0.5	< 2	7.83	35.0	29	10	37	7.67	10	< 1	0.07	< 10	5.26	654	5
S 09772	299	238	0.13	54.0	115	< 10	< 0.5	< 2	11.75	21.0	16	15	34	3.21	10	< 1	0.09	< 10	8.19	812	2
S 09773	299	238	0.05	0.6	20	< 10	< 0.5	< 2	13.45	5.5	4	9	8	1.56	20	< 1	0.04	< 10	9.36	755	2
S 09774	299	238	0.07	8.6	55	< 10	< 0.5	< 2	11.45	19.0	8	18	55	3.29	10	< 1	0.05	< 10	8.31	749	2
S 09775	299	238	0.12	11.4	160	10	< 0.5	< 2	11.60	26.0	6	12	62	5.54	10	< 1	0.04	< 10	8.24	715	3

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T: :CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU BLENDE
Comments:

Page N : 1-B
Tot. P. : 1
Date : 23-AUG-88
Invoice # : I-8821212
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821212

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 09679	299	238	0.01	1	60	3690	15	1	75	< 0.01	< 10	< 10	2	< 5	2040
S 09680	299	238	0.01	< 1	70	>10000	90	1	77	< 0.01	< 10	< 10	2	15	6160
S 09681	299	238	0.01	2	40	1115	25	1	93	< 0.01	< 10	< 10	1	< 5	543
S 09682	299	238	0.01	4	180	2030	15	2	135	< 0.01	< 10	< 10	3	< 5	793
S 09683	299	238	0.01	5	200	>10000	15	2	119	< 0.01	< 10	< 10	3	20	9840
S 09684	299	238	0.01	3	20	6600	10	< 1	70	< 0.01	< 10	< 10	2	15	6520
S 09685	299	238	0.01	3	250	3830	10	2	147	< 0.01	< 10	< 10	3	5	1915
S 09690	299	238	0.01	6	210	7570	15	1	119	< 0.01	< 10	< 10	2	20	>10000
S 09691	299	238	0.01	1	20	1250	5	< 1	64	< 0.01	< 10	< 10	2	< 5	1590
S 09692	299	238	0.01	11	230	500	10	3	141	< 0.01	< 10	< 10	5	< 5	539
S 09693	299	238	0.01	6	250	330	5	3	177	< 0.01	< 10	< 10	5	< 5	337
S 09694	299	238	0.01	5	280	516	5	3	158	< 0.01	< 10	< 10	6	< 5	2170
S 09695	299	238	0.01	4	170	1285	5	2	101	< 0.01	< 10	< 10	4	< 5	3470
S 09696	299	238	0.01	6	130	1020	10	2	93	< 0.01	< 10	< 10	3	< 5	629
S 09697	299	238	0.01	3	70	698	10	1	71	< 0.01	< 10	< 10	3	< 5	271
S 09751	299	238	0.01	10	230	476	15	3	125	< 0.01	< 10	< 10	3	< 5	211
S 09752	299	238	0.01	6	490	370	10	3	140	< 0.01	< 10	< 10	3	< 5	178
S 09753	299	238	0.01	9	410	702	10	3	136	< 0.01	< 10	< 10	5	< 5	249
S 09754	299	238	0.01	9	180	1860	20	2	137	< 0.01	< 10	< 10	4	< 5	2440
S 09755	299	238	0.01	14	170	9480	35	1	100	< 0.01	< 10	< 10	3	5	1890
S 09756	299	238	0.01	32	120	>10000	180	2	120	< 0.01	< 10	< 10	4	15	1820
S 09757	299	238	0.01	19	160	8270	30	3	129	< 0.01	< 10	< 10	6	15	6690
S 09758	299	238	0.01	8	150	4530	245	2	131	< 0.01	< 10	< 10	4	5	2970
S 09759	299	238	0.01	17	270	>10000	15	4	160	< 0.01	< 10	< 10	13	10	3870
S 09760	299	238	0.01	13	130	9440	15	3	101	< 0.01	< 10	< 10	10	5	5180
S 09761	299	238	0.01	16	60	>10000	35	1	61	< 0.01	< 10	< 10	6	30	>10000
S 09762	299	238	0.01	16	90	>10000	30	1	69	< 0.01	< 10	< 10	7	25	6190
S 09763	299	238	0.01	4	250	2770	5	2	98	< 0.01	< 10	< 10	9	< 5	1280
S 09764	299	238	0.01	8	140	2250	10	3	98	< 0.01	< 10	< 10	9	< 5	1095
S 09765	299	238	0.01	5	180	1870	5	2	101	< 0.01	< 10	< 10	5	< 5	444
S 09766	299	238	0.01	19	90	>10000	25	1	51	< 0.01	< 10	< 10	4	30	>10000
S 09767	299	238	0.01	31	100	7970	35	1	62	< 0.01	< 10	< 10	5	15	>10000
S 09768	299	238	0.01	94	160	5690	55	2	86	< 0.01	< 10	< 10	7	< 5	6880
S 09769	299	238	0.01	16	220	3510	20	2	99	< 0.01	< 10	< 10	5	< 5	7260
S 09770	299	238	0.01	47	210	>10000	55	2	81	< 0.01	< 10	< 10	7	25	>10000
S 09771	299	238	0.01	100	180	>10000	120	1	63	< 0.01	< 10	< 10	7	50	>10000
S 09772	299	238	0.01	47	70	>10000	80	1	48	< 0.01	< 10	< 10	4	35	>10000
S 09773	299	238	0.01	5	90	416	15	1	42	< 0.01	< 10	< 10	4	5	5530
S 09774	299	238	0.01	17	60	524	35	1	39	< 0.01	< 10	< 10	4	15	>10000
S 09775	299	238	0.02	31	80	892	40	1	39	< 0.01	< 10	< 10	6	10	>10000

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NDU BLENDE
Comments:

Date : 29-AUG-88
Invoice # : I-8821676
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821676

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %						
S 08320	208	--	< 0.002	0.06	0.06	0.77						
S 08321	208	--	< 0.002	0.04	0.10	0.32						
S 08322	208	--	< 0.002	0.12	0.58	0.48						
S 08323	208	--	< 0.002	0.04	0.10	1.04						
S 08324	208	--	< 0.002	0.03	0.08	0.17						
S 08325	208	--	< 0.002	< 0.01	0.02	0.02						
S 08326	208	--	< 0.002	0.09	0.25	0.69						
S 08327	208	--	< 0.002	< 0.01	0.04	0.10						
S 08328	208	--	< 0.002	< 0.01	0.03	0.17						
S 08329	208	--	< 0.002	< 0.01	0.01	0.03						
S 08330	208	--	< 0.002	< 0.01	0.06	0.02						
S 08331	208	--	< 0.002	0.01	0.06	0.06						
S 08332	208	--	< 0.002	0.03	0.06	0.07						
S 08333	208	--	< 0.002	< 0.01	0.18	0.34						
S 08334	208	--	< 0.002	0.03	0.16	0.14						
S 08335	208	--	< 0.002	0.10	0.29	0.38						
S 08336	208	--	< 0.002	0.04	0.23	0.11						
S 08337	208	--	< 0.002	0.05	0.22	0.35						
S 08338	208	--	< 0.002	0.04	0.22	0.17						
S 08339	208	--	< 0.002	0.01	0.08	0.23						
S 08340	208	--	< 0.002	0.02	0.09	0.18						
S 08341	208	--	< 0.002	0.13	0.55	0.38						
S 08342	208	--	< 0.002	0.03	0.10	0.04						
S 08343	208	--	< 0.002	0.01	0.10	0.03						
S 08344	208	--	< 0.002	0.03	0.16	0.02						
S 08345	208	--	< 0.002	0.04	0.25	0.01						
S 08346	208	--	< 0.002	0.19	0.50	0.50						
S 08347	208	--	< 0.002	0.80	2.37	2.77						
S 08348	208	--	< 0.002	0.38	0.62	1.15						
S 08349	208	--	< 0.002	0.07	0.09	0.25						
S 08350	208	--	< 0.002	0.03	0.07	0.02						
S 08351	208	--	< 0.002	0.16	0.35	0.08						
S 08352	208	--	< 0.002	0.04	0.10	0.10						
S 08353	208	--	< 0.002	0.06	0.12	0.13						
S 08354	208	--	< 0.002	0.19	0.25	0.98						
S 08355	208	--	< 0.002	1.49	2.10	2.77						
S 08356	208	--	< 0.002	0.22	0.33	0.40						
S 08357	208	--	< 0.002	0.17	0.22	0.57						
S 08358	208	--	< 0.002	0.04	0.06	0.07						
S 08359	208	--	< 0.002	< 0.01	< 0.01	< 0.01						

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NDU BLENDE
Comments:

Page : 1-A
Tot. Pages: 1
Date : 31-AUG-88
Invoice # : I-8821677
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821677

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 08320	299	238	0.33	1.8	25	40	< 0.5	< 2	12.05	8.0	< 1	32	21	1.03	< 10	2	0.15	< 10	8.01	867	< 1
S 08321	299	238	0.12	0.8	35	10	< 0.5	< 2	13.20	3.0	< 1	24	52	1.51	< 10	< 1	0.05	< 10	8.52	1195	< 1
S 08322	299	238	0.14	3.2	30	10	< 0.5	< 2	14.15	5.5	< 1	21	35	1.63	< 10	1	0.07	< 10	9.09	1310	< 1
S 08323	299	238	0.17	1.0	25	< 10	< 0.5	< 2	13.85	13.0	< 1	17	46	1.23	< 10	< 1	0.11	< 10	9.06	1115	< 1
S 08324	299	238	0.08	0.4	20	< 10	< 0.5	< 2	14.50	1.5	< 1	13	8	1.00	< 10	< 1	0.04	< 10	9.57	1010	< 1
S 08325	299	238	0.09	0.2	15	< 10	< 0.5	< 2	13.60	< 0.5	< 1	10	5	1.09	< 10	< 1	0.06	< 10	8.87	1115	< 1
S 08326	299	238	0.10	3.0	35	< 10	< 0.5	< 2	13.75	7.0	< 1	11	64	1.03	< 10	< 1	0.06	< 10	9.04	949	< 1
S 08327	299	238	0.13	0.2	15	< 10	< 0.5	< 2	13.35	0.5	< 1	10	8	0.96	< 10	2	0.09	< 10	8.78	894	< 1
S 08328	299	238	0.14	0.6	15	< 10	< 0.5	< 2	13.35	1.5	< 1	9	9	1.14	< 10	1	0.10	< 10	8.71	1005	< 1
S 08329	299	238	0.14	0.2	25	< 10	< 0.5	< 2	14.80	< 0.5	< 1	10	3	0.85	< 10	< 1	0.10	< 10	9.87	862	< 1
S 08330	299	238	0.06	0.4	25	< 10	< 0.5	< 2	14.45	< 0.5	< 1	8	3	1.07	< 10	< 1	0.04	< 10	9.33	1060	1
S 08331	299	238	0.04	0.2	20	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	7	4	1.10	< 10	< 1	0.03	< 10	9.83	1105	1
S 08332	299	238	0.11	0.8	25	< 10	< 0.5	< 2	12.55	2.0	1	9	7	1.33	< 10	< 1	0.08	< 10	7.99	1070	< 1
S 08333	299	238	0.06	1.2	25	< 10	< 0.5	< 2	14.65	3.0	< 1	13	10	1.04	< 10	< 1	0.04	< 10	9.52	1065	< 1
S 08334	299	238	0.03	0.2	35	< 10	< 0.5	< 2	>15.00	0.5	< 1	6	5	0.85	< 10	< 1	0.02	< 10	9.87	849	< 1
S 08335	299	238	0.06	0.6	15	< 10	< 0.5	< 2	14.20	1.0	< 1	8	5	1.26	< 10	< 1	0.05	< 10	9.05	1195	< 1
S 08336	299	238	0.50	3.0	25	10	< 0.5	< 2	11.75	4.5	< 1	17	78	1.19	< 10	< 1	0.35	< 10	7.50	1030	< 1
S 08337	299	238	0.24	0.8	15	< 10	< 0.5	< 2	13.85	1.0	< 1	8	11	1.21	< 10	< 1	0.18	< 10	8.89	1120	< 1
S 08338	299	238	0.16	0.4	45	< 10	< 0.5	< 2	14.25	3.5	1	10	19	1.32	< 10	< 1	0.11	< 10	9.16	1060	1
S 08339	299	238	0.13	0.8	15	< 10	< 0.5	< 2	11.95	2.5	< 1	6	9	1.31	< 10	< 1	0.09	< 10	7.56	1010	< 1
S 08340	299	238	0.16	0.2	40	10	< 0.5	< 2	12.20	1.5	2	12	10	1.35	< 10	< 1	0.09	< 10	7.86	1045	< 1
S 08341	299	238	0.16	2.6	105	< 10	< 0.5	< 2	13.25	4.0	17	10	43	2.28	< 10	< 1	0.09	< 10	8.26	1345	< 1
S 08342	299	238	0.30	1.0	50	< 10	< 0.5	< 2	13.25	< 0.5	3	10	4	1.89	< 10	< 1	0.19	< 10	8.23	1395	< 1
S 08343	299	238	0.15	0.2	15	< 10	< 0.5	< 2	14.50	< 0.5	< 1	11	2	1.95	< 10	< 1	0.10	< 10	8.99	1455	< 1
S 08344	299	238	0.09	0.6	25	< 10	< 0.5	< 2	14.50	< 0.5	< 1	8	2	2.51	< 10	< 1	0.05	< 10	8.72	1680	< 1
S 08345	299	238	0.09	1.0	15	< 10	< 0.5	< 2	14.25	< 0.5	< 1	6	< 1	2.88	< 10	< 1	0.05	< 10	8.37	1960	< 1
S 08346	299	238	0.09	6.2	40	< 10	0.5	< 2	13.60	5.0	< 1	9	25	3.35	< 10	< 1	0.04	< 10	7.76	2210	< 1
S 08347	299	238	0.09	27.2	45	< 10	< 0.5	< 2	11.35	34.0	3	10	58	1.31	< 10	< 1	0.06	< 10	7.27	784	< 1
S 08348	299	238	0.18	13.2	25	20	< 0.5	< 2	12.95	14.0	< 1	25	28	1.25	< 10	< 1	0.06	< 10	8.32	679	< 1
S 08349	299	238	0.25	1.8	30	20	< 0.5	< 2	>15.00	3.0	< 1	12	10	0.91	< 10	< 1	0.15	< 10	9.83	536	< 1
S 08350	299	238	0.14	0.2	25	10	< 0.5	< 2	14.90	< 0.5	< 1	7	7	0.94	< 10	< 1	0.08	< 10	9.59	644	< 1
S 08351	299	238	0.20	5.4	30	10	< 0.5	< 2	14.95	< 0.5	< 1	7	9	0.86	< 10	< 1	0.14	< 10	9.64	616	< 1
S 08352	299	238	0.09	0.8	30	< 10	< 0.5	< 2	>15.00	0.5	< 1	4	3	0.73	< 10	< 1	0.06	< 10	9.85	497	< 1
S 08353	299	238	0.16	1.8	25	10	< 0.5	< 2	14.40	1.0	< 1	7	6	0.85	< 10	< 1	0.12	< 10	9.28	564	< 1
S 08354	299	238	0.14	6.8	45	100	< 0.5	< 2	11.65	12.5	< 1	12	20	1.21	< 10	< 1	0.10	< 10	7.41	694	< 1
S 08355	299	238	0.08	52.0	70	10	< 0.5	< 2	13.35	36.5	< 1	25	106	1.95	< 10	< 1	0.05	< 10	8.33	1365	< 1
S 08356	299	238	0.12	8.8	40	10	< 0.5	< 2	13.05	6.0	< 1	5	12	0.95	< 10	< 1	0.09	< 10	8.47	548	< 1
S 08357	299	238	0.25	6.4	35	10	< 0.5	< 2	13.95	7.5	< 1	8	21	0.87	< 10	< 1	0.19	< 10	9.05	539	< 1
S 08358	299	238	0.28	1.0	25	20	< 0.5	< 2	13.35	< 0.5	< 1	15	9	0.78	< 10	< 1	0.17	< 10	9.00	531	< 1
S 08359	299	238	1.62	0.2	< 5	240	0.5	< 2	1.58	< 0.5	8	88	17	2.67	< 10	< 1	0.40	< 10	1.42	445	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T CHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : NIDU BLENDE
Comments:

Date :31-AUG-88
Invoice # :I-8821677
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821677

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 08320	299	238	0.02	1	180	466	< 5	2	109	0.03	< 10	< 10	8	20	6090
S 08321	299	238	0.02	5	120	746	< 5	2	113	0.01	< 10	< 10	5	10	2750
S 08322	299	238	0.02	4	180	4370	< 5	2	114	< 0.01	< 10	< 10	5	15	4250
S 08323	299	238	0.02	4	130	856	< 5	2	120	< 0.01	< 10	< 10	< 1	25	8260
S 08324	299	238	0.02	< 1	140	648	5	1	98	< 0.01	< 10	< 10	1	5	1730
S 08325	299	238	0.02	4	250	198	< 5	2	123	< 0.01	< 10	< 10	1	5	427
S 08326	299	238	0.02	3	210	1975	< 5	2	93	< 0.01	< 10	< 10	1	10	5460
S 08327	299	238	0.02	1	330	292	< 5	2	96	< 0.01	< 10	< 10	2	5	1065
S 08328	299	238	0.02	< 1	280	214	< 5	2	113	< 0.01	< 10	< 10	1	10	1560
S 08329	299	238	0.02	3	150	122	< 5	1	78	< 0.01	< 10	< 10	< 1	< 5	360
S 08330	299	238	0.02	< 1	130	410	5	2	73	< 0.01	< 10	< 10	< 1	5	161
S 08331	299	238	0.02	3	80	370	5	1	58	< 0.01	< 10	< 10	< 1	5	519
S 08332	299	238	0.01	7	90	712	5	2	140	< 0.01	< 10	< 10	1	10	1505
S 08333	299	238	0.02	1	130	1290	< 5	1	60	< 0.01	< 10	< 10	< 1	10	2650
S 08334	299	238	0.02	< 1	60	468	< 5	1	56	< 0.01	< 10	< 10	< 1	< 5	661
S 08335	299	238	0.02	1	150	1210	< 5	2	101	< 0.01	< 10	< 10	< 1	10	1210
S 08336	299	238	0.02	3	270	2360	10	2	161	< 0.01	< 10	< 10	5	10	3370
S 08337	299	238	0.02	3	150	1865	5	2	155	< 0.01	< 10	< 10	< 1	10	1095
S 08338	299	238	0.02	5	90	1725	5	2	151	< 0.01	< 10	< 10	< 1	10	2940
S 08339	299	238	0.01	4	120	678	< 5	2	149	< 0.01	< 10	< 10	1	10	1975
S 08340	299	238	0.02	7	100	700	5	2	141	< 0.01	< 10	< 10	3	10	1705
S 08341	299	238	0.02	33	90	4330	5	2	135	< 0.01	< 10	< 10	4	20	3170
S 08342	299	238	0.02	11	140	856	< 5	3	152	< 0.01	< 10	< 10	5	10	462
S 08343	299	238	0.02	5	90	782	5	2	111	< 0.01	< 10	< 10	4	10	297
S 08344	299	238	0.02	7	180	1260	< 5	4	113	< 0.01	< 10	< 10	8	15	201
S 08345	299	238	0.03	6	250	1835	< 5	5	122	< 0.01	< 10	< 10	10	15	139
S 08346	299	238	0.02	9	240	3720	5	4	157	< 0.01	< 10	< 10	10	30	3920
S 08347	299	238	0.02	10	150	>10000	15	1	154	< 0.01	< 10	< 10	1	45	>10000
S 08348	299	238	0.02	6	50	4720	10	1	108	0.01	< 10	< 10	5	25	8510
S 08349	299	238	0.02	4	20	792	5	1	138	0.01	< 10	< 10	5	10	2300
S 08350	299	238	0.02	1	50	678	35	2	129	< 0.01	< 10	< 10	4	< 5	381
S 08351	299	238	0.02	< 1	30	2660	5	1	104	< 0.01	< 10	< 10	1	5	732
S 08352	299	238	0.02	1	40	784	5	1	86	< 0.01	< 10	< 10	1	5	836
S 08353	299	238	0.03	< 1	100	922	5	1	106	< 0.01	< 10	< 10	1	5	1030
S 08354	299	238	0.02	4	170	1950	5	2	135	< 0.01	< 10	< 10	2	20	7680
S 08355	299	238	0.02	11	150	>10000	85	2	87	< 0.01	< 10	< 10	< 1	55	>10000
S 08356	299	238	0.02	< 1	90	3010	5	2	100	< 0.01	< 10	< 10	1	15	3890
S 08357	299	238	0.02	4	70	1890	5	1	105	< 0.01	< 10	< 10	1	15	4640
S 08358	299	238	0.02	1	40	350	< 5	2	91	0.01	< 10	< 10	4	5	600
S 08359	299	238	0.19	6	620	18	< 5	5	57	0.23	< 10	< 10	72	5	76

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: CHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Date : 30-AUG-88
Invoice # : I-8821693
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821693

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
S 08201	208	--	< 0.002	0.09	0.13	0.02
S 08202	208	--	< 0.002	0.10	0.03	0.01
S 08203	208	--	< 0.002	0.03	0.02	0.01
S 08204	208	--	< 0.002	0.01	0.01	0.01
S 08205	208	--	< 0.002	< 0.01	0.01	< 0.01
S 08206	208	--	< 0.002	0.01	0.01	< 0.01
S 08207	208	--	< 0.002	0.02	0.03	< 0.01
S 08208	208	--	< 0.002	0.03	0.01	< 0.01
S 08209	208	--	< 0.002	0.02	0.01	0.01
S 08210	208	--	< 0.002	0.03	0.03	0.02
S 08211	208	--	< 0.002	0.17	0.43	0.02
S 08212	208	--	< 0.002	0.28	0.63	0.03
S 08213	208	--	< 0.002	0.20	0.89	0.35
S 08214	208	--	< 0.002	0.06	0.15	0.02
S 08215	208	--	< 0.002	0.06	0.12	0.03
S 08216	208	--	< 0.002	0.04	0.07	0.02
S 08217	208	--	< 0.002	0.02	0.05	0.01
S 08218	208	--	< 0.002	0.17	0.29	0.07
S 08219	208	--	< 0.002	0.70	1.07	0.38
S 08220	208	--	< 0.002	1.01	1.34	0.22
S 08221	208	--	< 0.002	0.95	1.37	0.37
S 08222	208	--	< 0.002	0.35	0.82	0.26
S 08223	208	--	< 0.002	0.22	0.84	0.18
S 08224	208	--	< 0.002	0.12	0.49	0.09
S 08225	208	--	< 0.002	0.28	0.89	0.40
S 08226	208	--	< 0.002	0.25	0.71	0.25
S 08227	208	--	< 0.002	0.89	2.03	0.74
S 08228	208	--	< 0.002	1.21	2.50	1.54
S 08229	208	--	< 0.002	0.34	0.69	0.25
S 08230	208	--	< 0.002	1.41	2.31	0.96
S 08231	208	--	< 0.002	0.04	0.09	0.06
S 08232	208	--	< 0.002	0.03	0.06	0.03
S 08233	208	--	< 0.002	0.01	0.03	0.01
S 08234	208	--	< 0.002	0.16	0.54	0.40
S 08235	208	--	< 0.002	0.06	0.13	0.02
S 08236	208	--	< 0.002	0.03	0.09	0.02
S 08237	208	--	< 0.002	0.35	1.06	0.72
S 08238	208	--	< 0.002	0.12	0.37	0.06
S 08239	208	--	< 0.002	0.16	0.41	0.18
S 08240	208	--	< 0.002	0.67	1.17	1.18

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No :
Tot. Pages :3
Date :30-AUG-88
Invoice # :I-8821693
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821693

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %						
S 08241	208	--	< 0.002	0.22	0.38	0.21						
S 08242	208	--	< 0.002	0.16	0.36	0.19						
S 08243	208	--	< 0.002	0.50	1.33	0.96						
S 08244	208	--	< 0.002	0.19	0.48	0.48						
S 08245	208	--	< 0.002	0.04	0.08	0.12						
S 08246	208	--	< 0.002	0.06	0.24	0.30						
S 08247	208	--	< 0.002	0.02	0.04	0.20						
S 08248	208	--	< 0.002	< 0.01	0.01	0.09						
S 08249	208	--	< 0.002	0.06	0.06	0.77						
S 08250	208	--	< 0.002	0.07	0.07	1.43						
S 08251	208	--	< 0.002	0.03	0.05	0.48						
S 08252	208	--	< 0.002	0.10	0.20	1.39						
S 08253	208	--	< 0.002	0.09	0.16	0.98						
S 08254	208	--	< 0.002	0.09	0.10	1.64						
S 08255	208	--	< 0.002	0.04	0.04	0.33						
S 08256	208	--	< 0.002	0.05	0.06	0.11						
S 08257	208	--	< 0.002	0.04	0.01	0.11						
S 08258	208	--	< 0.002	0.03	0.03	0.07						
S 08259	208	--	< 0.002	0.01	< 0.01	0.01						
S 08260	208	--	< 0.002	0.01	< 0.01	0.03						
S 08261	208	--	< 0.002	< 0.01	< 0.01	0.02						
S 08262	208	--	< 0.002	< 0.01	< 0.01	0.01						
S 08263	208	--	< 0.002	< 0.01	< 0.01	0.02						
S 08264	208	--	< 0.002	< 0.01	< 0.01	0.01						
S 08265	208	--	< 0.002	< 0.01	< 0.01	0.02						
S 08266	208	--	< 0.002	0.01	< 0.01	0.08						
S 08267	208	--	< 0.002	0.01	< 0.01	0.03						
S 08360	208	--	< 0.002	0.09	0.20	0.19						
S 08361	208	--	< 0.002	0.47	1.08	0.51						
S 08362	208	--	< 0.002	0.22	0.58	0.52						
S 08363	208	--	< 0.002	0.15	0.40	0.67						
S 08364	208	--	< 0.002	0.36	0.91	1.70						
S 08365	208	--	< 0.002	0.31	0.82	0.92						
S 08366	208	--	< 0.002	0.04	0.07	0.27						
S 08367	208	--	< 0.002	0.09	0.25	0.43						
S 08368	208	--	< 0.002	0.36	0.98	0.92						
S 08369	208	--	< 0.002	0.22	0.49	1.59						
S 08370	208	--	< 0.002	0.70	1.98	2.13						
S 08371	208	--	< 0.002	0.34	0.89	0.65						
S 08372	208	--	< 0.002	0.47	0.98	1.77						

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date : 30-AUG-88
Invoice # : I-8821693
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821693

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Ag oz/T	Pb %	Zn %
S 08373	208	--	< 0.002	0.16	0.37	0.59
S 08374 + 08375	208	--	< 0.002	0.29	0.63	0.74
S 08376	208	--	< 0.002	0.17	0.38	0.48
S 08377	208	--	< 0.002	0.05	0.11	0.14
S 08378	208	--	< 0.002	0.06	0.11	0.09
S 08379	208	--	< 0.002	0.13	0.30	0.18
S 08380	208	--	< 0.002	0.60	1.68	0.89
S 08381	208	--	< 0.002	0.09	0.32	0.25
S 08382	208	--	< 0.002	0.09	0.20	0.11
S 08383	208	--	< 0.002	0.13	0.37	0.05
S 08384	208	--	< 0.002	0.13	0.38	0.15
S 08385	208	--	< 0.002	0.03	0.10	0.05
S 08386	208	--	< 0.002	0.25	1.31	0.25
S 08387	208	--	< 0.002	0.02	0.10	0.09
S 08388	208	--	< 0.002	0.04	0.20	0.13
S 08389	208	--	< 0.002	0.16	0.43	0.14
S 08390	208	--	< 0.002	0.15	0.40	0.22
S 08391	208	--	< 0.002	0.69	1.45	1.13
S 08392	208	--	< 0.002	1.49	2.14	1.99
S 08393	208	--	< 0.002	0.45	1.06	0.59
S 08394	208	--	< 0.002	0.36	0.66	0.48
S 08395	208	--	< 0.002	0.74	1.22	0.52
S 08396	208	--	< 0.002	0.71	1.37	0.69
S 08397	208	--	< 0.002	0.04	0.08	0.05
S 08398	208	--	< 0.002	0.04	0.06	0.02
S 08399	208	--	< 0.002	0.45	0.75	0.24
S 08400	208	--	< 0.002	1.36	2.20	0.40

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T: :CHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page N : 1-A
Tot. P. : 3
Date : 31-AUG-88
Invoice # : I-8821694
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 08201	299	238	0.72	3.4	55	50	1.0	< 2	7.18	0.5	11	30	16	1.24	< 10	1	0.46	< 10	4.70	392	1
S 08202	299	238	0.75	2.6	50	30	1.0	< 2	7.50	< 0.5	11	27	9	1.23	< 10	1	0.51	< 10	4.88	410	< 1
S 08203	299	238	0.80	0.2	15	20	1.0	< 2	7.20	< 0.5	12	28	4	1.38	< 10	1	0.57	< 10	4.68	353	< 1
S 08204	299	238	0.95	0.4	10	20	1.0	< 2	8.63	< 0.5	< 1	25	< 1	1.57	< 10	< 1	0.71	< 10	5.81	375	< 1
S 08205	299	238	1.01	0.4	20	20	1.0	< 2	8.43	< 0.5	< 1	26	< 1	1.29	< 10	< 1	0.75	< 10	5.81	366	1
S 08206	299	238	1.12	1.2	10	20	1.0	< 2	7.75	< 0.5	2	21	< 1	1.43	< 10	1	0.84	< 10	5.35	332	< 1
S 08207	299	238	1.10	0.6	10	50	1.0	< 2	7.12	< 0.5	3	27	9	1.77	< 10	< 1	0.74	< 10	4.85	316	< 1
S 08208	299	238	1.15	0.6	< 5	40	1.0	< 2	8.22	< 0.5	2	24	5	1.43	< 10	< 1	0.78	< 10	4.77	328	< 1
S 08209	299	238	0.82	0.2	10	30	0.5	< 2	7.21	< 0.5	< 1	16	3	1.03	< 10	< 1	0.56	< 10	4.45	362	< 1
S 08210	299	238	0.90	0.6	10	20	0.5	< 2	7.14	< 0.5	1	21	7	1.08	< 10	< 1	0.60	< 10	4.41	411	< 1
S 08211	299	238	0.23	5.8	5	10	< 0.5	< 2	9.27	0.5	< 1	11	4	1.16	< 10	< 1	0.16	< 10	5.78	482	< 1
S 08212	299	238	0.49	8.8	20	10	< 0.5	< 2	8.55	< 0.5	2	15	7	1.16	< 10	< 1	0.35	< 10	5.36	410	< 1
S 08213	299	238	0.31	6.4	50	10	< 0.5	< 2	9.50	4.5	5	18	11	1.38	< 10	< 1	0.22	< 10	5.90	658	< 1
S 08214	299	238	0.35	1.8	15	10	< 0.5	< 2	10.40	< 0.5	< 1	11	6	0.98	< 10	< 1	0.26	< 10	6.51	493	< 1
S 08215	299	238	0.35	1.4	15	10	< 0.5	< 2	11.30	< 0.5	< 1	14	5	0.95	< 10	< 1	0.26	< 10	7.13	472	< 1
S 08216	299	238	0.36	0.8	10	10	< 0.5	< 2	11.65	< 0.5	< 1	9	6	0.99	< 10	< 1	0.26	< 10	7.31	529	< 1
S 08217	299	238	0.51	0.2	20	30	0.5	< 2	10.30	< 0.5	1	20	13	1.29	< 10	< 1	0.29	< 10	6.74	592	< 1
S 08218	299	238	0.55	5.2	20	20	0.5	< 2	9.61	1.0	6	16	15	1.15	< 10	< 1	0.36	< 10	6.32	475	< 1
S 08219	299	238	0.26	24.0	30	10	< 0.5	< 2	10.80	6.0	4	30	52	0.88	< 10	< 1	0.18	< 10	7.14	436	< 1
S 08220	299	238	0.04	34.8	30	< 10	< 0.5	< 2	12.95	3.5	< 1	25	63	0.93	< 10	< 1	0.02	< 10	8.65	530	< 1
S 08221	299	238	0.37	32.8	15	10	< 0.5	< 2	8.34	6.5	5	20	76	0.85	< 10	< 1	0.25	< 10	5.38	357	< 1
S 08222	299	238	0.22	11.8	25	< 10	< 0.5	< 2	9.99	4.0	4	10	19	1.13	< 10	< 1	0.15	< 10	6.38	508	< 1
S 08223	299	238	0.17	7.2	30	< 10	< 0.5	< 2	12.65	2.5	< 1	6	9	0.96	< 10	< 1	0.12	< 10	8.15	591	< 1
S 08224	299	238	0.23	4.0	30	< 10	< 0.5	< 2	12.50	0.5	< 1	6	15	0.97	< 10	< 1	0.17	< 10	8.04	639	< 1
S 08225	299	238	0.44	8.6	35	20	< 0.5	< 2	11.40	4.5	1	16	58	0.97	< 10	< 1	0.25	< 10	7.67	550	< 1
S 08226	299	238	0.11	8.0	25	< 10	< 0.5	< 2	13.05	3.5	< 1	7	22	0.88	< 10	< 1	0.06	< 10	8.77	575	< 1
S 08227	299	238	0.17	30.6	55	< 10	< 0.5	< 2	11.55	10.5	1	8	35	1.10	< 10	< 1	0.11	< 10	7.77	511	< 1
S 08228	299	238	0.08	42.0	45	< 10	< 0.5	< 2	13.50	23.0	< 1	4	47	1.11	< 10	< 1	0.05	< 10	9.15	640	< 1
S 08229	299	238	0.06	11.8	40	< 10	< 0.5	< 2	14.80	3.5	< 1	2	19	0.97	< 10	< 1	0.05	< 10	9.97	629	< 1
S 08230	299	238	0.08	4.6	55	< 10	< 0.5	< 2	12.30	15.5	< 1	7	42	1.08	< 10	< 1	0.07	< 10	8.31	502	< 1
S 08231	299	238	0.62	1.2	25	10	0.5	< 2	8.20	0.5	1	18	7	1.14	< 10	< 1	0.40	< 10	5.28	644	< 1
S 08232	299	238	0.21	1.0	30	< 10	< 0.5	< 2	8.38	< 0.5	3	11	7	1.23	< 10	< 1	0.15	< 10	5.31	638	< 1
S 08233	299	238	0.30	0.6	20	< 10	< 0.5	< 2	8.93	< 0.5	< 1	16	2	1.23	< 10	< 1	0.23	< 10	5.66	700	< 1
S 08234	299	238	0.31	5.6	15	< 10	< 0.5	< 2	8.60	6.0	< 1	15	23	1.12	< 10	< 1	0.23	< 10	5.55	603	< 1
S 08235	299	238	0.26	1.2	15	10	< 0.5	< 2	7.54	< 0.5	1	14	5	0.99	< 10	< 1	0.17	< 10	4.98	450	< 1
S 08236	299	238	0.73	1.2	25	10	0.5	< 2	7.24	< 0.5	7	26	3	1.12	< 10	< 1	0.48	< 10	4.82	414	< 1
S 08237	299	238	0.70	10.6	35	10	0.5	< 2	8.14	11.0	10	25	19	1.32	< 10	< 1	0.47	< 10	5.42	506	< 1
S 08238	299	238	0.28	3.2	30	< 10	0.5	< 2	9.10	1.0	5	6	8	1.43	< 10	< 1	0.20	< 10	5.96	640	< 1
S 08239	299	238	0.05	6.2	30	< 10	< 0.5	< 2	14.90	2.0	< 1	9	7	1.18	< 10	< 1	0.05	< 10	10.05	872	1
S 08240	299	238	< 0.01	23.0	20	< 10	< 0.5	< 2	14.65	16.0	< 1	9	109	1.11	< 10	< 1	0.01	< 10	9.98	751	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date : 31-AUG-88
Invoice # : I-8821694
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 08201	299	238	0.02	21	510	970	10	5	53	0.02	< 10	< 10	15	5	177
S 08202	299	238	0.02	26	460	1010	10	5	55	0.01	< 10	< 10	10	5	174
S 08203	299	238	0.02	14	520	238	5	5	61	< 0.01	< 10	< 10	10	10	65
S 08204	299	238	0.02	10	450	116	< 5	4	87	< 0.01	< 10	< 10	14	10	37
S 08205	299	238	0.02	9	490	128	5	4	84	< 0.01	< 10	< 10	13	5	20
S 08206	299	238	0.02	9	500	84	5	5	86	0.01	< 10	< 10	14	5	18
S 08207	299	238	0.02	7	280	210	5	5	77	0.02	< 10	< 10	20	5	32
S 08208	299	238	0.02	5	310	130	5	5	106	0.02	< 10	< 10	20	< 5	23
S 08209	299	238	0.02	2	360	134	< 5	5	67	0.01	< 10	< 10	10	< 5	52
S 08210	299	238	0.02	3	380	252	5	4	63	0.01	< 10	< 10	12	< 5	117
S 08211	299	238	0.02	3	250	3320	10	3	60	< 0.01	< 10	< 10	2	< 5	125
S 08212	299	238	0.02	6	290	5110	10	4	55	< 0.01	< 10	< 10	7	< 5	418
S 08213	299	238	0.02	13	270	6970	10	3	61	< 0.01	< 10	< 10	4	5	2940
S 08214	299	238	0.02	4	220	1320	5	3	78	< 0.01	< 10	< 10	5	< 5	246
S 08215	299	238	0.02	2	200	1025	5	3	80	< 0.01	< 10	< 10	5	< 5	268
S 08216	299	238	0.02	< 1	130	690	5	3	90	< 0.01	< 10	< 10	6	< 5	186
S 08217	299	238	0.02	6	230	348	5	3	83	0.02	< 10	< 10	9	< 5	77
S 08218	299	238	0.02	8	260	2320	10	3	78	0.01	< 10	< 10	7	5	651
S 08219	299	238	0.02	9	190	8350	55	2	77	< 0.01	< 10	< 10	5	5	3290
S 08220	299	238	0.02	9	60	>10000	75	< 1	50	< 0.01	< 10	< 10	< 1	5	1920
S 08221	299	238	0.01	10	260	>10000	55	3	69	< 0.01	< 10	< 10	6	5	3100
S 08222	299	238	0.01	10	230	6960	15	3	96	< 0.01	< 10	< 10	< 1	10	2300
S 08223	299	238	0.01	1	80	6740	10	2	100	< 0.01	< 10	< 10	< 1	< 5	1560
S 08224	299	238	0.02	6	90	3940	5	2	98	< 0.01	< 10	< 10	< 1	< 5	808
S 08225	299	238	0.01	5	110	6620	10	2	91	0.02	< 10	< 10	7	5	3330
S 08226	299	238	0.01	2	40	5640	10	1	81	< 0.01	< 10	< 10	1	10	2210
S 08227	299	238	0.01	10	70	>10000	25	1	74	< 0.01	< 10	< 10	1	15	6020
S 08228	299	238	0.02	11	70	>10000	35	1	76	< 0.01	< 10	< 10	< 1	30	>10000
S 08229	299	238	0.02	2	10	6010	15	1	79	< 0.01	< 10	< 10	< 1	5	2510
S 08230	299	238	0.01	10	90	>10000	50	1	84	< 0.01	< 10	< 10	1	20	8340
S 08231	299	238	0.01	9	380	1525	5	4	187	< 0.01	< 10	< 10	8	5	976
S 08232	299	238	0.01	12	350	766	5	3	204	< 0.01	< 10	< 10	3	5	456
S 08233	299	238	0.01	4	260	426	5	3	217	< 0.01	< 10	< 10	2	5	191
S 08234	299	238	0.01	7	310	4270	5	3	219	< 0.01	< 10	< 10	2	15	3460
S 08235	299	238	0.01	9	310	1030	< 5	3	208	< 0.01	< 10	< 10	1	< 5	203
S 08236	299	238	0.01	13	360	754	5	4	213	< 0.01	< 10	< 10	7	5	234
S 08237	299	238	0.02	15	340	8420	10	4	213	< 0.01	< 10	< 10	6	15	6460
S 08238	299	238	0.01	6	300	3150	5	4	232	< 0.01	< 10	< 10	< 1	10	808
S 08239	299	238	0.02	4	40	3040	10	1	126	< 0.01	< 10	< 10	1	10	1545
S 08240	299	238	0.02	10	20	8360	35	< 1	99	< 0.01	< 10	< 10	< 1	25	9010

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. : 2-A
Tot. Pa. : 3
Date : 31-AUG-88
Invoice # : I-8821694
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 08241	299	238	0.09	8.0	30	10	< 0.5	< 2	13.00	3.0	< 1	22	60	1.20	< 10	< 1	0.02	< 10	8.51	836	< 1
S 08242	299	238	0.03	5.8	25	< 10	< 0.5	< 2	14.30	2.5	< 1	34	24	1.03	< 10	< 1	0.01	< 10	9.43	744	< 1
S 08243	299	238	0.04	17.0	45	< 10	< 0.5	< 2	>15.00	12.5	< 1	9	24	1.25	< 10	< 1	0.02	< 10	10.30	857	1
S 08244	299	238	0.28	6.2	50	< 10	0.5	< 2	13.80	5.5	3	17	69	3.13	< 10	< 1	0.13	< 10	8.25	2940	< 1
S 08245	299	238	0.19	1.0	35	< 10	0.5	< 2	12.10	1.0	< 1	8	17	2.62	< 10	< 1	0.12	< 10	7.35	2120	< 1
S 08246	299	238	0.11	1.4	35	< 10	< 0.5	< 2	11.30	3.5	< 1	19	27	1.83	< 10	< 1	0.08	< 10	7.27	1250	< 1
S 08247	299	238	0.17	0.2	35	< 10	< 0.5	< 2	10.95	2.5	< 1	6	24	1.43	< 10	< 1	0.13	< 10	7.16	919	< 1
S 08248	299	238	0.16	0.2	30	< 10	< 0.5	< 2	13.85	0.5	< 1	9	8	1.17	< 10	< 1	0.13	< 10	9.25	918	< 1
S 08249	299	238	0.15	0.6	50	< 10	< 0.5	< 2	13.65	8.0	< 1	12	55	1.83	< 10	< 1	0.12	< 10	9.14	1015	< 1
S 08250	299	238	0.13	2.8	65	< 10	0.5	< 2	13.55	18.5	< 1	5	162	2.40	< 10	< 1	0.10	< 10	8.96	1175	< 1
S 08251	299	238	0.09	1.0	30	< 10	< 0.5	< 2	13.70	6.0	< 1	18	31	1.68	< 10	< 1	0.07	< 10	8.96	1340	< 1
S 08252	299	238	0.09	3.2	45	< 10	< 0.5	< 2	13.75	20.0	< 1	5	54	1.96	< 10	< 1	0.07	< 10	8.93	1485	< 1
S 08253	299	238	0.41	2.8	50	30	< 0.5	< 2	10.75	18.5	< 1	29	70	1.79	< 10	< 1	0.18	< 10	7.21	1160	< 1
S 08254	299	238	0.19	2.6	55	10	< 0.5	< 2	12.45	21.0	1	30	119	2.42	< 10	1	0.10	< 10	8.25	1505	< 1
S 08255	299	238	0.14	1.0	50	< 10	0.5	< 2	12.00	3.5	< 1	36	35	3.32	< 10	< 1	0.06	< 10	7.49	1685	< 1
S 08256	299	238	0.66	0.8	55	10	0.5	< 2	8.34	1.0	7	119	15	3.12	< 10	< 1	0.40	< 10	5.12	1405	< 1
S 08257	299	238	0.56	0.2	75	10	0.5	< 2	11.30	1.0	5	29	14	3.03	< 10	< 1	0.35	< 10	7.16	1760	< 1
S 08258	299	238	0.33	0.2	65	10	0.5	< 2	14.45	< 0.5	< 1	17	8	2.53	< 10	< 1	0.21	< 10	9.64	1295	< 1
S 08259	299	238	0.12	0.2	35	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	10	3	1.46	< 10	< 1	0.08	< 10	11.20	1310	< 1
S 08260	299	238	0.09	0.2	40	< 10	< 0.5	< 2	>15.00	< 0.5	< 1	10	2	1.79	< 10	< 1	0.06	< 10	10.90	1180	< 1
S 08261	299	238	0.19	0.2	15	10	< 0.5	< 2	13.70	< 0.5	< 1	18	5	1.75	< 10	< 1	0.09	< 10	9.10	1385	< 1
S 08262	299	238	0.18	0.2	15	10	< 0.5	< 2	13.30	< 0.5	< 1	14	5	1.16	< 10	< 1	0.09	< 10	9.08	976	< 1
S 08263	299	238	0.20	0.2	10	20	< 0.5	< 2	9.86	< 0.5	< 1	16	10	0.93	< 10	< 1	0.06	< 10	6.77	733	< 1
S 08264	299	238	0.10	0.2	10	10	< 0.5	6	3.55	< 0.5	< 1	10	7	0.40	10	< 1	0.02	< 10	2.43	284	< 1
S 08265	299	238	0.08	0.2	< 5	10	< 0.5	2	2.61	< 0.5	< 1	7	6	0.31	10	< 1	0.01	< 10	1.79	212	< 1
S 08266	299	238	0.11	0.2	10	10	< 0.5	< 2	6.73	< 0.5	< 1	14	6	0.68	10	< 1	0.03	< 10	4.75	514	< 1
S 08267	299	238	0.06	0.2	20	< 10	< 0.5	< 2	5.48	< 0.5	< 1	9	3	0.53	10	< 1	0.03	< 10	3.84	412	< 1
S 08360	299	238	0.24	1.6	< 5	< 10	< 0.5	< 2	14.25	2.0	< 1	6	4	0.76	20	< 1	0.19	< 10	9.09	618	< 1
S 08361	299	238	0.06	13.8	< 5	< 10	< 0.5	< 2	15.55	7.0	< 1	6	13	0.69	20	< 1	0.04	< 10	9.94	646	< 1
S 08362	299	238	0.28	6.4	10	< 10	< 0.5	< 2	11.75	13.0	< 1	10	6	0.72	20	< 1	0.21	< 10	7.58	514	< 1
S 08363	299	238	0.27	5.0	25	30	< 0.5	< 2	13.45	8.5	< 1	29	21	0.86	< 10	1	0.08	< 10	9.37	564	< 1
S 08364	299	238	0.55	12.0	50	20	0.5	< 2	7.09	20.5	6	29	33	1.18	< 10	1	0.29	< 10	4.87	624	< 1
S 08365	299	238	0.10	8.4	30	< 10	< 0.5	< 2	14.60	9.0	< 1	11	11	0.80	< 10	< 1	0.05	< 10	10.10	616	< 1
S 08366	299	238	0.06	0.4	25	< 10	< 0.5	< 2	>15.00	4.5	< 1	9	4	0.64	< 10	< 1	0.04	< 10	10.65	570	< 1
S 08367	299	238	0.04	3.4	30	< 10	< 0.5	< 2	>15.00	5.5	< 1	9	5	0.72	< 10	< 1	0.02	< 10	10.65	660	< 1
S 08368	299	238	0.06	11.2	20	< 10	< 0.5	< 2	>15.00	12.5	< 1	7	16	0.75	< 10	1	0.04	< 10	10.65	645	< 1
S 08369	299	238	0.06	8.2	35	< 10	< 0.5	< 2	>15.00	27.0	< 1	11	26	1.52	< 10	1	0.04	< 10	10.35	1445	< 1
S 08370	299	238	0.10	24.6	50	< 10	< 0.5	< 2	13.35	28.5	< 1	17	29	2.31	< 10	1	0.07	< 10	9.16	905	< 1
S 08371	299	238	0.08	11.8	25	< 10	< 0.5	< 2	13.00	10.0	< 1	23	9	0.88	< 10	< 1	0.07	< 10	8.91	656	< 1
S 08372	299	238	0.08	16.2	30	30	< 0.5	< 2	13.15	22.0	< 1	18	10	0.90	< 10	2	0.06	< 10	9.04	669	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T .CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date :31-AUG-88
Invoice # :I-8821694
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 08241	299	238	0.02	4	40	3030	15	< 1	106	< 0.01	< 10	< 10	4	15	1865
S 08242	299	238	0.02	4	10	2900	10	< 1	92	< 0.01	< 10	< 10	1	10	1665
S 08243	299	238	0.02	11	40	9790	15	< 1	99	< 0.01	< 10	< 10	2	25	7290
S 08244	299	238	0.02	15	80	3940	5	2	129	< 0.01	< 10	< 10	5	25	4190
S 08245	299	238	0.02	10	80	890	5	2	109	< 0.01	< 10	< 10	2	15	1335
S 08246	299	238	0.01	7	50	1835	5	1	67	< 0.01	< 10	< 10	2	15	2490
S 08247	299	238	0.01	6	110	372	< 5	2	82	< 0.01	< 10	< 10	1	10	1725
S 08248	299	238	0.02	3	40	200	5	1	85	< 0.01	< 10	< 10	< 1	10	903
S 08249	299	238	0.02	11	70	504	< 5	1	83	< 0.01	< 10	< 10	1	25	6090
S 08250	299	238	0.02	21	90	550	5	2	83	< 0.01	< 10	< 10	2	40	>10000
S 08251	299	238	0.02	5	60	382	< 5	1	83	< 0.01	< 10	< 10	2	20	4390
S 08252	299	238	0.02	11	150	1510	5	2	85	< 0.01	< 10	< 10	2	40	>10000
S 08253	299	238	0.01	5	120	1110	< 5	2	70	0.03	< 10	< 10	9	30	8180
S 08254	299	238	0.02	14	90	710	5	2	64	0.01	< 10	< 10	3	35	>10000
S 08255	299	238	0.02	11	60	292	< 5	2	71	< 0.01	< 10	< 10	3	25	3310
S 08256	299	238	0.02	20	150	512	5	4	50	< 0.01	< 10	< 10	5	15	1355
S 08257	299	238	0.02	23	140	132	5	2	93	< 0.01	< 10	< 10	4	15	1170
S 08258	299	238	0.02	12	40	196	5	1	73	< 0.01	< 10	< 10	3	15	741
S 08259	299	238	0.02	3	< 10	50	< 5	1	78	< 0.01	< 10	< 10	1	10	214
S 08260	299	238	0.02	3	< 10	34	< 5	1	56	< 0.01	< 10	< 10	1	10	322
S 08261	299	238	0.02	8	170	2	< 5	1	82	0.01	< 10	< 10	6	15	149
S 08262	299	238	0.02	5	10	14	5	1	62	< 0.01	< 10	< 10	3	5	96
S 08263	299	238	0.01	5	60	10	< 5	1	43	0.01	< 10	< 10	5	5	86
S 08264	299	238	< 0.01	4	50	2	< 5	< 1	15	0.01	< 10	< 10	3	< 5	42
S 08265	299	238	< 0.01	1	60	2	< 5	< 1	11	0.01	< 10	< 10	2	< 5	31
S 08266	299	238	0.01	4	50	6	< 5	1	25	< 0.01	< 10	< 10	2	5	78
S 08267	299	238	< 0.01	5	40	< 2	< 5	< 1	19	< 0.01	< 10	< 10	1	< 5	63
S 08360	299	238	0.02	4	110	1630	10	2	30	< 0.01	< 10	< 10	5	< 5	1560
S 08361	299	238	0.02	2	50	9110	25	1	26	< 0.01	< 10	< 10	1	5	4540
S 08362	299	238	0.02	6	170	4990	15	2	23	< 0.01	< 10	< 10	5	5	4520
S 08363	299	238	0.02	5	50	2920	5	1	22	0.03	< 10	< 10	7	15	5220
S 08364	299	238	0.01	18	310	7830	25	3	20	0.01	< 10	< 10	8	35	>10000
S 08365	299	238	0.02	4	50	6310	10	< 1	22	< 0.01	< 10	< 10	< 1	20	7470
S 08366	299	238	0.02	< 1	< 10	774	5	< 1	22	< 0.01	< 10	< 10	< 1	10	2620
S 08367	299	238	0.02	3	< 10	1870	5	< 1	22	< 0.01	< 10	< 10	< 1	10	3690
S 08368	299	238	0.02	4	10	7310	10	< 1	19	< 0.01	< 10	< 10	< 1	20	7170
S 08369	299	238	0.03	3	50	3650	10	1	32	< 0.01	< 10	< 10	< 1	35	>10000
S 08370	299	238	0.02	7	110	>10000	25	1	22	< 0.01	< 10	< 10	2	45	>10000
S 08371	299	238	0.02	3	120	7470	15	1	23	< 0.01	< 10	< 10	< 1	15	5710
S 08372	299	238	0.02	3	70	7250	15	1	22	< 0.01	< 10	< 10	< 1	35	>10000

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date : 31-AUG-88
Invoice # : I-8821694
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
S 08373	299	238	0.15	6.2	25	20	< 0.5	< 2	8.66	7.0	< 1	16	11	1.07	< 10	< 1	0.07	< 10	5.95	627	< 1
S 08374 + 08375	299	238	0.24	9.2	20	10	0.5	< 2	9.08	9.0	< 1	23	15	0.99	< 10	< 1	0.15	< 10	6.27	572	< 1
S 08376	299	238	0.22	5.6	10	10	< 0.5	< 2	9.89	7.5	< 1	17	11	0.91	< 10	< 1	0.15	< 10	6.86	592	< 1
S 08377	299	238	0.07	1.4	30	< 10	< 0.5	< 2	12.95	1.5	< 1	11	3	0.75	< 10	< 1	0.04	< 10	9.14	491	< 1
S 08378	299	238	0.05	1.6	20	< 10	< 0.5	< 2	12.50	1.0	< 1	11	3	0.70	< 10	< 1	0.04	< 10	8.80	436	< 1
S 08379	299	238	0.03	4.8	15	< 10	< 0.5	< 2	13.20	2.0	< 1	16	3	0.63	< 10	< 1	0.02	< 10	9.29	445	< 1
S 08380	299	238	0.03	18.2	20	< 10	< 0.5	< 2	10.90	13.0	< 1	13	6	0.87	< 10	< 1	0.01	< 10	7.63	487	< 1
S 08381	299	238	0.05	3.8	20	< 10	< 0.5	< 2	15.00	3.5	< 1	11	6	0.91	< 10	< 1	0.04	< 10	10.50	611	< 1
S 08382	299	238	0.08	2.0	25	< 10	< 0.5	< 2	12.65	1.5	< 1	11	3	0.77	< 10	< 1	0.06	< 10	8.88	500	< 1
S 08383	299	238	0.03	4.4	20	< 10	< 0.5	< 2	13.50	0.5	< 1	15	2	0.67	< 10	< 1	0.02	< 10	9.53	479	< 1
S 08384	299	238	0.04	4.8	25	< 10	< 0.5	< 2	12.70	1.0	< 1	8	4	0.73	< 10	< 1	0.02	< 10	8.99	461	< 1
S 08385	299	238	0.03	0.6	35	< 10	< 0.5	< 2	13.30	< 0.5	< 1	6	2	0.74	< 10	< 1	0.03	< 10	9.39	464	< 1
S 08386	299	238	0.04	8.6	25	< 10	< 0.5	< 2	12.45	4.0	< 1	8	5	0.81	< 10	< 1	0.04	< 10	8.76	526	< 1
S 08387	299	238	0.02	1.2	20	< 10	< 0.5	< 2	11.70	2.0	< 1	14	1	0.67	< 10	< 1	0.03	< 10	8.27	521	< 1
S 08388	299	238	0.01	1.8	25	< 10	< 0.5	< 2	13.90	1.0	< 1	6	1	0.70	< 10	< 1	0.02	< 10	9.76	524	< 1
S 08389	299	238	0.06	6.0	25	< 10	< 0.5	< 2	13.15	1.0	< 1	5	5	0.88	< 10	< 1	0.05	< 10	9.18	662	< 1
S 08390	299	238	0.05	5.6	25	< 10	< 0.5	< 2	13.60	2.5	< 1	6	6	0.87	< 10	< 1	0.05	< 10	9.52	628	< 1
S 08391	299	238	0.11	23.2	35	< 10	< 0.5	< 2	11.30	14.5	< 1	4	45	1.18	< 10	< 1	0.09	< 10	7.89	681	< 1
S 08392	299	238	0.13	50.0	65	< 10	< 0.5	< 2	13.00	25.0	< 1	7	106	1.43	< 10	< 1	0.10	< 10	9.12	640	< 1
S 08393	299	238	0.10	16.6	45	< 10	< 0.5	< 2	13.70	7.5	< 1	7	11	1.10	< 10	< 1	0.08	< 10	9.62	604	< 1
S 08394	299	238	0.14	11.2	20	10	< 0.5	< 2	13.40	6.0	< 1	11	11	0.85	< 10	< 1	0.06	< 10	9.40	496	< 1
S 08395	299	238	0.14	26.2	40	10	< 0.5	< 2	13.80	6.0	< 1	6	8	1.30	< 10	< 1	0.08	< 10	9.64	619	< 1
S 08396	299	238	0.31	24.0	35	30	0.5	< 2	6.80	12.0	12	15	20	0.98	< 10	< 1	0.21	< 10	4.59	405	< 1
S 08397	299	238	0.58	0.8	35	10	0.5	< 2	6.75	1.0	21	16	5	1.07	< 10	< 1	0.39	< 10	4.61	350	< 1
S 08398	299	238	0.59	0.6	15	10	0.5	< 2	7.06	< 0.5	13	16	2	1.08	< 10	< 1	0.40	< 10	4.82	346	< 1
S 08399	299	238	0.40	14.4	50	40	0.5	< 2	7.45	3.5	14	12	9	1.09	< 10	< 1	0.28	< 10	5.00	397	< 1
S 08400	299	238	0.24	46.0	45	10	< 0.5	< 2	9.73	6.5	13	15	26	1.10	< 10	< 1	0.17	< 10	6.67	425	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date : 31-AUG-88
Invoice # : I-8821694
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8821694

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
S 08373	299	238	0.01	9	240	2900	5	2	22	0.01	< 10	< 10	3	10	4710
S 08374 + 08375	299	238	0.01	7	210	5660	10	2	24	< 0.01	< 10	< 10	3	10	5930
S 08376	299	238	0.01	7	230	3540	5	2	25	< 0.01	< 10	< 10	5	10	4240
S 08377	299	238	0.01	< 1	60	1070	< 5	1	24	< 0.01	< 10	< 10	2	< 5	1340
S 08378	299	238	0.01	5	30	1015	< 5	1	23	< 0.01	< 10	< 10	2	< 5	815
S 08379	299	238	0.01	4	< 10	2550	5	< 1	23	< 0.01	< 10	< 10	1	< 5	1455
S 08380	299	238	0.01	4	40	>10000	15	< 1	20	< 0.01	< 10	< 10	1	10	6780
S 08381	299	238	0.01	4	10	3040	5	1	25	< 0.01	< 10	< 10	1	5	2300
S 08382	299	238	0.01	3	40	1700	< 5	1	28	< 0.01	< 10	< 10	1	5	1085
S 08383	299	238	0.01	< 1	< 10	2920	5	< 1	24	< 0.01	< 10	< 10	2	< 5	555
S 08384	299	238	0.01	4	10	2760	5	< 1	25	< 0.01	< 10	< 10	< 1	< 5	1210
S 08385	299	238	0.01	2	30	810	< 5	1	26	< 0.01	< 10	< 10	< 1	< 5	454
S 08386	299	238	0.01	2	50	9730	10	1	29	< 0.01	< 10	< 10	< 1	5	1995
S 08387	299	238	0.01	1	10	1070	5	< 1	24	< 0.01	< 10	< 10	< 1	< 5	817
S 08388	299	238	0.01	2	10	1635	5	< 1	27	< 0.01	< 10	< 10	< 1	< 5	1035
S 08389	299	238	0.01	4	60	3580	5	1	31	< 0.01	< 10	< 10	< 1	5	1210
S 08390	299	238	0.01	7	60	3450	5	1	31	< 0.01	< 10	< 10	< 1	5	1920
S 08391	299	238	0.01	10	140	>10000	20	2	26	< 0.01	< 10	< 10	< 1	25	9160
S 08392	299	238	0.02	10	100	>10000	65	1	25	< 0.01	< 10	< 10	< 1	35	>10000
S 08393	299	238	0.02	4	30	8600	15	1	26	< 0.01	< 10	< 10	< 1	15	5110
S 08394	299	238	0.02	3	30	5000	10	1	24	0.01	< 10	< 10	4	10	3830
S 08395	299	238	0.02	9	50	9630	25	1	26	< 0.01	< 10	< 10	< 1	10	4660
S 08396	299	238	0.01	26	380	>10000	30	3	34	< 0.01	< 10	< 10	4	15	6360
S 08397	299	238	0.01	26	380	1185	10	4	44	< 0.01	< 10	< 10	7	5	805
S 08398	299	238	0.01	18	390	722	5	4	44	< 0.01	< 10	< 10	7	< 5	306
S 08399	299	238	0.01	31	320	6390	20	3	43	< 0.01	< 10	< 10	5	5	2100
S 08400	299	238	0.01	26	180	>10000	50	2	46	< 0.01	< 10	< 10	2	5	3400

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To HER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : NIDU (BLENDE)
Comments:

Page No
Tot. Pa
Date :22-SEP-88
Invoice # :I-8821763
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8821763

SAMPLE DESCRIPTION	PREP CODE		Sn %	Ge %							
S09176 - S09177	214	--	< 0.01	0.003							
S09184 - S09189	214	--	< 0.01	0.002							
S09604 - S09615	214	--	< 0.01	0.003							
S09993 - S09996	214	--	< 0.01	0.005							

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To 'HER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No
Tot. Pag. 1
Date :05-OCT-89
Invoice # :I-8925876
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8925876

SAMPLE DESCRIPTION	PREP CODE		In NAA ppm	Ge %
H 53380	214	--	3	0.001
K 7772	214	--	-----	0.001
SO9993-96	214	--	10	-----
T 24503	214	--	10	-----

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. :-A
Tot. Pages :2
Date :27-JUN-89
Invoice # :I-8918167
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8918167

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
K 7442	201	238	0.52	2.8	40	40	1.0	< 2	2.07	3.5	14	11	27	5.02	< 10	5	0.08	20	1.24	1750	1
K 7443	201	238	1.39	2.4	35	570	1.0	< 2	2.23	1.5	20	25	41	5.63	< 10	< 1	0.16	10	1.37	3200	3
K 7444	201	238	0.69	< 0.2	30	240	0.5	< 2	1.44	< 0.5	13	12	22	4.15	< 10	< 1	0.08	20	0.74	2440	< 1
K 7445	201	238	1.09	1.0	35	290	1.0	< 2	2.34	0.5	19	18	46	5.18	< 10	< 1	0.14	10	1.47	2890	2
K 7446	201	238	1.50	0.2	25	120	0.5	< 2	0.11	< 0.5	11	25	19	4.16	< 10	< 1	0.09	20	0.35	1165	4
K 7447	201	238	1.08	0.2	30	250	0.5	< 2	4.53	< 0.5	10	25	37	4.20	< 10	< 1	0.09	< 10	2.83	2140	1
K 7448	201	238	1.22	1.0	30	240	0.5	< 2	1.31	1.0	14	24	35	4.47	< 10	< 1	0.14	20	0.79	2480	1
K 7449	201	238	1.17	0.6	105	160	0.5	< 2	0.73	< 0.5	26	20	50	10.50	< 10	< 1	0.07	30	0.53	9130	5
K 7450	201	238	0.23	0.4	30	100	< 0.5	< 2	12.50	1.0	10	5	66	3.55	< 10	< 1	0.05	< 10	7.76	3380	1
K 7451	201	238	0.13	0.2	5	90	< 0.5	< 2	>15.00	< 0.5	4	4	24	2.76	< 10	< 1	0.01	< 10	9.30	2870	< 1
K 7452	201	238	0.17	< 0.2	< 5	180	< 0.5	< 2	14.55	< 0.5	< 1	5	8	2.75	< 10	< 1	0.01	< 10	9.21	3400	< 1
K 7453	201	238	1.49	< 0.2	10	260	0.5	< 2	3.87	< 0.5	9	28	28	4.46	< 10	1	0.04	< 10	2.78	2880	1
K 7454	201	238	0.95	0.2	30	480	< 0.5	< 2	6.81	< 0.5	10	19	42	4.85	< 10	< 1	0.04	< 10	4.46	4150	1
K 7455	201	238	0.43	1.4	< 5	820	< 0.5	< 2	2.21	0.5	6	6	40	1.90	< 10	< 1	0.10	10	1.11	875	4
K 7456	201	238	0.66	0.8	70	480	< 0.5	< 2	0.12	< 0.5	23	12	73	4.99	< 10	4	0.20	20	0.12	385	26
K 7457	201	238	0.28	0.2	20	350	< 0.5	< 2	12.95	0.5	6	8	57	3.43	< 10	< 1	0.03	< 10	8.08	2940	1
K 7458	201	238	0.22	0.4	30	320	< 0.5	< 2	13.15	< 0.5	6	7	65	3.60	< 10	< 1	0.02	< 10	8.26	3110	1
K 7459	201	238	1.41	0.4	35	420	0.5	< 2	0.81	0.5	13	26	41	6.21	< 10	< 1	0.07	20	0.56	3870	2
K 7460	201	238	0.80	0.4	45	530	0.5	< 2	1.92	< 0.5	18	11	69	6.75	< 10	1	0.10	20	0.84	7450	9
K 7461	201	238	1.28	0.6	115	480	0.5	< 2	2.13	< 0.5	18	24	81	9.10	< 10	< 1	0.07	10	1.20	6860	4
K 7462	201	238	0.16	0.2	15	70	< 0.5	< 2	14.35	< 0.5	7	7	69	3.70	< 10	< 1	0.01	< 10	8.71	3790	11
K 7463	201	238	0.64	0.6	55	420	< 0.5	< 2	6.28	< 0.5	16	15	91	6.66	< 10	1	0.06	< 10	3.84	6540	10
K 7464	201	238	0.48	1.4	25	90	0.5	< 2	7.84	1.0	8	11	41	3.60	< 10	< 1	0.06	< 10	4.87	2710	< 1
K 7465	201	238	0.95	4.0	50	110	0.5	< 2	2.53	8.0	18	19	59	5.02	< 10	1	0.07	10	1.59	2840	1
K 7466	201	238	0.48	1.8	35	80	0.5	< 2	7.50	3.0	11	15	41	3.52	< 10	2	0.06	< 10	4.69	2580	1
K 7467	201	238	0.49	< 0.2	20	130	< 0.5	< 2	7.49	< 0.5	8	20	35	3.30	< 10	1	0.07	< 10	4.52	2260	1
K 7468	201	238	1.19	< 0.2	55	280	0.5	< 2	1.34	< 0.5	15	25	51	6.77	< 10	< 1	0.07	20	0.93	5340	3
K 7469	201	238	0.80	< 0.2	25	120	0.5	< 2	7.34	< 0.5	20	22	56	5.05	< 10	< 1	0.10	< 10	4.72	3440	1
K 7470	201	238	0.70	0.6	25	50	0.5	< 2	3.43	< 0.5	12	18	34	4.00	< 10	< 1	0.05	< 10	2.12	1625	< 1
K 7471	201	238	0.26	33.0	250	10	< 0.5	< 2	6.88	19.5	22	8	70	7.51	< 10	3	0.03	< 10	4.38	1070	< 1
K 7472	201	238	0.71	5.8	165	40	0.5	< 2	5.74	16.0	21	15	54	5.15	< 10	2	0.08	< 10	3.90	1385	2
K 7473	201	238	0.89	2.4	210	90	0.5	< 2	4.37	12.0	25	18	73	5.70	< 10	3	0.16	< 10	2.89	1670	3
K 7474	201	238	0.70	< 0.2	20	60	0.5	< 2	3.45	< 0.5	15	14	37	2.71	< 10	2	0.16	< 10	2.23	1360	< 1
K 7475	201	238	0.78	< 0.2	15	60	0.5	< 2	3.85	< 0.5	15	16	45	2.99	< 10	< 1	0.15	< 10	2.50	1340	1
K 7476	201	238	1.91	< 0.2	30	100	0.5	< 2	1.32	< 0.5	24	50	136	5.11	< 10	< 1	0.12	20	2.32	2510	4
K 7477	201	238	1.33	1.0	30	50	0.5	< 2	4.92	1.0	22	36	86	4.07	< 10	2	0.10	< 10	3.98	2060	1
T 24801	201	238	0.56	< 0.2	25	60	0.5	< 2	0.28	< 0.5	8	6	15	1.93	10	< 1	0.06	10	0.38	645	< 1
T 24802	201	238	0.61	< 0.2	25	40	0.5	< 2	3.82	< 0.5	18	16	29	3.76	< 10	< 1	0.10	< 10	2.20	1845	< 1
T 24803	201	238	1.03	< 0.2	20	60	0.5	< 2	3.46	< 0.5	14	17	25	3.47	< 10	< 1	0.07	< 10	2.74	860	< 1
T 24804	201	238	1.04	< 0.2	< 5	50	0.5	< 2	2.95	< 0.5	11	14	39	2.42	< 10	1	0.10	10	2.16	380	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T \CHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 27-JUN-89
Invoice # : I-8918167
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918167

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
K 7442	201	238	< 0.01	25	550	882	5	6	17	0.01	< 10	< 10	19	10	1545
K 7443	201	238	0.01	36	1580	360	10	6	18	0.01	< 10	< 10	59	< 10	658
K 7444	201	238	< 0.01	20	770	38	< 5	6	18	0.01	< 10	< 10	20	< 10	320
K 7445	201	238	0.01	29	1140	186	5	7	33	0.01	< 10	< 10	39	< 10	414
K 7446	201	238	< 0.01	20	790	102	< 5	3	11	0.03	< 10	< 10	51	< 10	226
K 7447	201	238	0.01	21	950	92	5	5	30	0.03	< 10	< 10	33	10	340
K 7448	201	238	0.01	22	1190	598	5	4	29	0.03	< 10	< 10	34	< 10	760
K 7449	201	238	< 0.01	43	1060	192	5	9	16	0.03	< 10	< 10	50	< 10	506
K 7450	201	238	0.01	16	270	212	5	3	31	< 0.01	< 10	10	9	10	684
K 7451	201	238	0.01	11	120	38	5	1	29	< 0.01	< 10	< 10	5	10	100
K 7452	201	238	0.01	12	130	12	5	1	18	< 0.01	< 10	< 10	5	10	68
K 7453	201	238	0.01	27	650	30	< 5	5	17	0.04	< 10	< 10	41	< 10	120
K 7454	201	238	0.01	25	760	80	5	3	20	0.02	< 10	< 10	27	10	222
K 7455	201	238	< 0.01	33	1750	70	5	2	60	< 0.01	< 10	< 10	9	< 10	426
K 7456	201	238	< 0.01	39	2110	150	10	1	312	0.01	< 10	< 10	29	< 10	136
K 7457	201	238	0.01	27	360	80	10	2	36	0.01	< 10	< 10	12	10	270
K 7458	201	238	0.01	16	280	90	5	2	32	0.01	< 10	< 10	10	< 10	178
K 7459	201	238	< 0.01	29	1580	208	5	4	11	0.02	< 10	< 10	41	< 10	492
K 7460	201	238	< 0.01	33	1900	52	15	2	14	0.01	< 10	< 10	25	< 10	222
K 7461	201	238	0.01	42	1350	116	10	4	14	0.03	< 10	< 10	39	< 10	388
K 7462	201	238	0.01	25	190	24	10	2	49	< 0.01	< 10	< 10	20	10	96
K 7463	201	238	0.01	44	810	62	10	4	20	0.01	< 10	< 10	23	20	348
K 7464	201	238	0.01	17	620	476	10	5	27	0.01	< 10	< 10	16	10	988
K 7465	201	238	< 0.01	31	840	1985	10	5	14	0.02	< 10	< 10	28	20	6490
K 7466	201	238	0.01	25	540	862	10	4	23	0.01	< 10	< 10	16	10	2060
K 7467	201	238	0.01	23	600	54	10	3	26	0.01	< 10	< 10	14	10	190
K 7468	201	238	< 0.01	30	860	42	5	5	11	0.02	< 10	< 10	32	10	298
K 7469	201	238	0.01	29	700	32	5	7	23	0.01	< 10	< 10	23	20	170
K 7470	201	238	< 0.01	24	670	276	5	7	38	0.01	< 10	< 10	25	10	368
K 7471	201	238	< 0.01	47	400	>10000	60	4	42	< 0.01	< 10	< 10	10	30	>10000
K 7472	201	238	0.01	53	500	3540	15	5	29	0.01	< 10	< 10	19	20	9430
K 7473	201	238	0.01	59	640	628	20	5	19	0.01	< 10	< 10	21	20	7430
K 7474	201	238	< 0.01	21	630	38	5	4	19	0.02	< 10	< 10	18	< 10	234
K 7475	201	238	< 0.01	25	770	36	5	5	29	0.02	< 10	< 10	19	< 10	216
K 7476	201	238	< 0.01	43	760	44	5	10	15	0.06	< 10	< 10	51	< 10	322
K 7477	201	238	0.01	38	780	418	10	8	29	0.05	< 10	< 10	44	10	1000
T 24801	201	238	< 0.01	12	370	42	< 5	3	4	< 0.01	< 10	< 10	6	< 10	74
T 24802	201	238	0.01	26	1040	64	5	8	27	< 0.01	< 10	< 10	11	10	144
T 24803	201	238	0.01	22	880	6	5	8	35	0.01	< 10	< 10	11	< 10	82
T 24804	201	238	< 0.01	22	1010	32	5	6	28	< 0.01	< 10	< 10	8	< 10	74

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 2-A
Tot. Pages: 2
Date : 27-JUN-89
Invoice # : I-8918167
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918167

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 24805	201	238	0.38	< 0.2	10	50	0.5	< 2	6.91	< 0.5	15	18	36	2.67	< 10	< 1	0.08	< 10	4.03	1230	1
T 24806	201	238	0.25	< 0.2	10	30	0.5	< 2	9.66	< 0.5	11	8	22	2.94	< 10	< 1	0.04	< 10	5.68	1460	< 1
T 24807	201	238	0.89	< 0.2	25	180	< 0.5	< 2	9.16	< 0.5	39	48	56	5.15	< 10	1	0.36	< 10	5.03	285	2
T 24809	201	238	0.29	< 0.2	10	300	< 0.5	< 2	>15.00	< 0.5	< 1	14	7	2.14	< 10	< 1	0.10	< 10	9.72	525	6
T 24811	217	238	0.56	< 0.2	215	560	< 0.5	< 2	0.39	1.0	< 1	18	103	>15.00	< 10	3	0.08	10	0.32	520	52
T 24812	201	238	0.42	0.2	5	460	0.5	< 2	4.70	< 0.5	12	17	12	3.49	< 10	1	0.07	< 10	2.48	1675	< 1
T 24813	201	238	0.74	0.4	20	200	0.5	< 2	1.28	< 0.5	16	14	37	4.24	10	< 1	0.08	30	0.77	950	< 1
T 24814	201	238	1.67	3.2	30	290	0.5	< 2	0.76	< 0.5	13	21	40	4.45	20	< 1	0.09	30	1.15	505	< 1
T 24815	201	238	1.04	0.4	35	240	0.5	< 2	0.35	< 0.5	14	14	33	4.90	20	1	0.13	30	0.44	1100	< 1
T 24816	201	238	0.22	< 0.2	10	360	< 0.5	< 2	12.95	< 0.5	7	9	35	2.62	< 10	1	0.03	< 10	7.86	1085	1
T 24817	201	238	1.38	0.4	25	100	< 0.5	< 2	0.93	< 0.5	26	24	96	4.75	20	< 1	0.16	30	1.17	2430	1
T 24818	201	238	1.68	0.6	30	110	0.5	< 2	0.77	< 0.5	36	33	85	4.89	20	1	0.23	30	1.40	5820	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: CHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 27-JUN-89
Invoice # : I-8918167
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918167

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 24805	201	238	0.01	23	950	96	5	7	50	< 0.01	< 10	< 10	10	< 10	184
T 24806	201	238	0.01	20	740	120	5	7	64	< 0.01	< 10	< 10	8	10	162
T 24807	201	238	0.01	90	2760	8	5	11	77	< 0.01	< 10	< 10	49	20	92
T 24809	201	238	0.01	21	170	20	5	1	75	< 0.01	< 10	< 10	21	10	86
T 24811	217	238	< 0.01	40	1470	418	15	5	14	< 0.01	< 10	20	24	< 50	4800
T 24812	201	238	0.01	19	810	2	5	7	84	< 0.01	< 10	< 10	14	10	82
T 24813	201	238	< 0.01	31	980	8	< 5	7	20	0.01	< 10	< 10	19	< 10	112
T 24814	201	238	< 0.01	31	1150	1735	< 5	9	21	0.01	< 10	< 10	22	< 10	204
T 24815	201	238	< 0.01	22	1150	28	< 5	8	10	0.01	< 10	< 10	18	< 10	142
T 24816	201	238	0.01	17	560	50	5	3	67	< 0.01	< 10	< 10	18	10	158
T 24817	201	238	0.01	32	1060	78	< 5	8	16	0.06	< 10	< 10	52	< 10	250
T 24818	201	238	0.01	38	990	18	< 5	8	18	0.06	< 10	< 10	38	< 10	156

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-A
Tot. Pages: 1
Date : 27-JUN-89
Invoice # : I-8918168
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918168

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 24808	205	238	0.31	1.8	280	1680	< 0.5	< 2	2.09	< 0.5	< 1	11	68	>15.00	110	< 1	0.03	10	1.45	360	19
T 24810	205	238	0.46	< 0.2	5	810	< 0.5	< 2	14.80	< 0.5	1	17	13	2.27	< 10	< 1	0.19	< 10	8.79	805	2

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-B
Tot. Pages: 1
Date : 27-JUN-89
Invoice # : I-8918168
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918168

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 24808	205	238	< 0.01	30	330	318	< 5	3	15	< 0.01	< 10	20	8	10	92
T 24810	205	238	0.02	11	430	24	5	2	71	< 0.01	< 10	< 10	14	10	96

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1
Tot. Pages: 1
Date : 25-JUN-89
Invoice # : I-8918169
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918169

SAMPLE DESCRIPTION	PREP CODE		Ag oz/T	Pb %	Zn %
K 7771	208	--	1.04	2.71	1.08
K 7772	208	--	12.80	36.1	11.60
K 7779	208	--	0.90	4.07	5.56
K 7780	208	--	0.08	0.23	0.17
K 7781	208	--	0.73	0.64	1.83

ALL ASSAY DETERMINATIONS ARE PERFORMED OR SUPERVISED BY B.C. CERTIFIED ASSAYERS

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 28-JUN-89
Invoice # : I-8918281
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918281

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
K 7486	201	238	1.90	< 0.2	30	100	< 0.5	< 2	0.47	< 0.5	36	18	86	6.20	20	< 1	0.12	40	0.94	3130	< 1
K 7487	201	238	1.63	< 0.2	25	170	< 0.5	< 2	0.62	< 0.5	27	23	104	4.94	10	< 1	0.10	30	0.93	2410	1
K 7489	201	238	0.66	0.6	45	50	< 0.5	< 2	7.09	4.0	17	15	50	4.95	< 10	< 1	0.06	< 10	4.49	3000	1
K 7490	201	238	0.70	0.2	65	60	< 0.5	< 2	5.20	< 0.5	27	12	36	4.39	10	< 1	0.11	< 10	3.32	2330	1
K 7491	201	238	1.63	0.2	65	110	< 0.5	< 2	2.22	1.0	34	19	122	6.40	20	2	0.14	20	1.89	4320	1
K 7492	201	238	0.67	0.2	20	70	< 0.5	< 2	7.79	< 0.5	18	13	38	3.00	< 10	< 1	0.08	< 10	4.88	1475	< 1
K 7493	201	238	1.80	0.4	55	50	0.5	4	0.23	< 0.5	42	15	111	5.95	20	1	0.19	30	0.89	3670	1
K 7494	201	238	1.87	< 0.2	40	200	< 0.5	< 2	0.89	< 0.5	112	19	97	4.73	20	2	0.17	30	1.08	>10000	4
K 7495	201	238	1.75	< 0.2	50	120	< 0.5	6	1.64	< 0.5	39	22	89	4.93	20	< 1	0.17	30	1.75	3320	< 1
K 7496	201	238	1.53	< 0.2	30	80	< 0.5	6	1.22	< 0.5	30	19	98	4.65	20	< 1	0.12	30	1.44	1480	< 1
K 7497	201	238	1.85	< 0.2	35	90	< 0.5	12	0.71	< 0.5	38	22	136	5.58	20	< 1	0.13	20	1.51	1740	< 1
K 7498	201	238	1.77	< 0.2	40	130	< 0.5	< 2	0.33	< 0.5	59	11	159	7.16	10	3	0.11	20	1.07	2270	1
K 7499	201	238	2.01	< 0.2	40	140	< 0.5	4	0.67	< 0.5	23	29	115	4.25	10	< 1	0.11	20	0.93	1235	2
T 24819	201	238	1.26	< 0.2	35	30	< 0.5	< 2	2.87	< 0.5	43	40	213	7.58	10	1	0.06	10	2.33	3910	2
T 24820	201	238	0.24	< 0.2	25	70	< 0.5	< 2	7.91	< 0.5	5	4	24	3.22	< 10	1	0.04	< 10	4.61	3120	< 1
T 24821	201	238	1.30	< 0.2	35	100	< 0.5	2	0.61	< 0.5	19	22	44	3.39	10	< 1	0.28	30	1.28	855	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page . . : 1-B
Tot. Pages: 1
Date : 28-JUN-89
Invoice # : I-8918281
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918281

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
K 7486	201	238	< 0.01	37	810	16	10	7	18	< 0.01	< 10	< 10	22	< 10	76
K 7487	201	238	0.01	30	920	16	5	7	23	0.06	< 10	< 10	37	< 10	228
K 7489	201	238	0.01	26	610	464	5	6	24	0.01	< 10	< 10	20	< 10	2910
K 7490	201	238	0.01	29	580	40	10	6	24	0.01	< 10	< 10	18	< 10	242
K 7491	201	238	0.01	37	860	258	10	8	24	0.01	< 10	< 10	30	< 10	1570
K 7492	201	238	0.01	21	710	44	5	4	45	0.01	< 10	< 10	21	< 10	124
K 7493	201	238	< 0.01	41	690	12	10	6	15	< 0.01	< 10	< 10	18	< 10	78
K 7494	201	238	0.01	198	710	22	5	6	33	0.02	< 10	< 10	30	< 10	132
K 7495	201	238	0.01	47	720	42	5	6	22	0.02	< 10	< 10	29	< 10	248
K 7496	201	238	< 0.01	42	710	14	5	9	16	0.03	< 10	< 10	68	< 10	172
K 7497	201	238	< 0.01	54	680	22	5	11	13	0.06	< 10	< 10	106	< 10	226
K 7498	201	238	< 0.01	95	830	16	10	15	9	0.03	< 10	< 10	150	< 10	84
K 7499	201	238	< 0.01	30	1370	24	10	5	19	0.02	< 10	< 10	44	< 10	100
T 24819	201	238	< 0.01	81	750	22	10	15	17	< 0.01	< 10	< 10	58	< 10	84
T 24820	201	238	0.01	9	530	32	5	4	15	< 0.01	< 10	< 10	9	< 10	294
T 24821	201	238	0.01	31	660	36	5	5	10	0.04	< 10	< 10	29	< 10	206

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-A
Tot. Pages: 1
Date : 28-JUN-89
Invoice # : I-8918282
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918282

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
K 7488	205	238	2.03	0.6	75	40	< 0.5	6	0.07	< 0.5	37	30	56	4.45	10	< 1	0.38	20	1.28	235	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BIENDE
Comments:

Page No. : 1-B
Tot. Pages: 1
Date : 28-JUN-89
Invoice # : I-8918282
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918282

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
K 7488	205	238	0.01	29	300	26	10	3	4	< 0.01	< 10	< 10	23	< 10	50

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 26-JUN-89
Invoice # : I-8918283
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918283

SAMPLE DESCRIPTION	PREP CODE		Ag oz/T	Pb %	Zn %
H 53375	208	--	0.38	0.06	0.25
H 53376	208	--	0.44	1.48	17.80
H 53378	208	--	0.92	8.55	4.92
H 53379	208	--	0.20	0.06	7.94
H 53380	208	--	0.06	0.01	4.60
BLENDE 12 ZONE	208	--	0.26	1.57	7.68

ALL ASSAY DETERMINATIONS ARE PERFORMED OR SUPERVISED BY BC CERTIFIED ASSAYERS

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.

125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-A
Tot. P : 1
Date : 4-JUL-89
Invoice # : I-8918705
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918705

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 24851	201 238	0.35	1.4	105	90	< 0.5	10	3.57	< 0.5	37	8	240	3.86	< 10	< 1	0.08	10	1.93	2060	3
T 24852	201 238	1.20	1.0	105	160	< 0.5	< 2	1.10	< 0.5	44	11	175	7.03	10	< 1	0.19	60	0.52	3140	3
T 24853	201 238	1.11	0.8	70	80	< 0.3	4	0.91	< 0.5	48	19	182	5.56	10	< 1	0.09	30	0.97	2540	2
T 24854	201 238	0.65	< 0.2	50	40	< 0.5	6	5.15	< 0.5	18	11	27	3.04	< 10	< 1	0.11	< 10	3.11	2180	< 1
T 24855	201 238	1.27	< 0.2	45	130	< 0.5	8	1.59	< 0.5	37	17	71	5.42	10	< 1	0.10	30	1.58	2620	1
T 24856	201 238	0.58	< 0.2	55	60	< 0.5	< 2	4.21	< 0.5	33	3	38	4.37	< 10	< 1	0.11	20	2.31	1775	2
T 24858	201 238	0.38	< 0.2	35	70	< 0.5	< 2	5.80	< 0.5	26	4	50	2.88	< 10	< 1	0.13	< 10	3.37	2040	< 1
T 24859	201 238	1.30	< 0.2	65	180	< 0.5	< 2	0.85	< 0.5	20	26	29	6.84	< 10	< 1	0.05	30	0.53	5290	2
T 24860	201 238	1.98	< 0.2	35	40	< 0.5	< 2	5.28	< 0.5	11	19	31	2.72	< 10	< 1	0.04	< 10	3.52	1355	< 1
T 24861	201 238	1.35	0.2	50	140	< 0.5	< 2	1.27	< 0.5	19	20	81	4.94	10	< 1	0.09	30	1.19	3380	2
T 24862	201 238	2.51	0.4	60	110	< 0.5	< 2	0.59	< 0.5	39	29	448	8.59	< 10	< 1	0.13	10	1.37	3280	1
T 24863	201 238	0.61	< 0.2	100	100	< 0.5	< 2	2.82	< 0.5	25	7	25	9.65	< 10	< 1	0.06	10	1.70	7710	3
T 24864	201 238	1.00	< 0.2	35	90	< 0.5	< 2	0.56	< 0.5	10	19	31	4.20	< 10	< 1	0.04	20	0.46	1375	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Page # : 1-B
Tot. # : 1
Date : 4-JUL-89
Invoice # : I-8918705
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918705

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 24851	201 238	< 0.01	34	770	74	20	5	74	< 0.01	< 10	< 10	10	< 10	284
T 24852	201 238	< 0.01	28	2540	100	20	8	74	0.01	< 10	< 10	23	< 10	234
T 24853	201 238	< 0.01	40	940	96	20	9	19	0.01	< 10	< 10	36	< 10	178
T 24854	201 238	0.01	20	1060	14	10	5	35	< 0.01	10	< 10	10	< 10	38
T 24855	201 238	< 0.01	45	1340	42	10	9	17	0.03	10	< 10	53	< 10	110
T 24856	201 238	0.01	20	2160	12	10	5	46	0.01	< 10	< 10	27	< 10	54
T 24858	201 238	< 0.01	22	1050	18	5	4	38	< 0.01	< 10	< 10	9	< 10	42
T 24859	201 238	< 0.01	32	750	66	15	8	18	0.03	< 10	< 10	27	< 10	200
T 24860	201 238	< 0.01	17	650	134	10	4	17	0.08	< 10	< 10	45	< 10	478
T 24861	201 238	0.01	29	830	114	10	7	14	0.05	< 10	< 10	41	< 10	256
T 24862	201 238	0.01	57	760	54	20	24	12	0.04	< 10	< 10	142	< 10	274
T 24863	201 238	< 0.01	52	1080	10	20	9	19	0.01	< 10	< 10	26	< 10	86
T 24864	201 238	< 0.01	21	660	4	10	4	14	0.04	< 10	< 10	28	< 10	70

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1
Tot. Pages: 1
Date : 29-JUN-89
Invoice # : I-8918706
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8918706

SAMPLE DESCRIPTION	PREP CODE		Au oz/T	Pb %	Zn %
T 24857	208	--	< 0.002	< 0.01	< 0.01
T 24865	208	--	< 0.002	0.83	8.12
T 24866	208	--	0.002	0.22	0.74
T 24867	208	--	< 0.002	5.16	8.01
T 24868	208	--	< 0.002	0.17	7.84

ALL ASSAY DETERMINATIONS ARE PERFORMED OR SUPERVISED BY B.C CERTIFIED ASSAYERS

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-A
Tot. Pages: 9
Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23201	201 238	1.08	< 0.2	10	90	< 0.5	< 2	0.92	< 0.5	13	20	28	2.90	< 10	< 1	0.21	30	0.96	845	< 1
23202	201 238	0.81	< 0.2	20	130	< 0.5	< 2	0.95	< 0.5	14	12	27	6.41	< 10	2	0.09	30	0.55	4550	< 1
23203	201 238	1.13	< 0.2	20	130	0.5	< 2	1.19	< 0.5	12	16	30	4.02	< 10	< 1	0.06	20	0.51	2130	< 1
23204	201 238	0.66	0.2	20	100	< 0.5	< 2	1.02	< 0.5	12	10	32	4.82	< 10	< 1	0.07	20	0.45	2850	1
23205	201 238	0.84	0.2	25	90	< 0.5	< 2	0.59	< 0.5	14	12	34	4.43	< 10	< 1	0.10	30	0.34	2200	< 1
23206	201 238	1.22	0.2	25	120	0.5	< 2	1.93	< 0.5	19	14	30	5.06	< 10	< 1	0.38	30	1.48	2850	< 1
23207	201 238	0.69	0.4	45	120	< 0.5	< 2	1.44	< 0.5	21	12	31	5.20	< 10	< 1	0.09	30	0.70	3930	< 1
23208	201 238	0.38	0.8	25	90	0.5	4	3.65	< 0.5	17	6	42	3.31	< 10	< 1	0.12	10	2.03	2190	< 1
23209	201 238	0.48	1.0	20	90	0.5	< 2	2.44	< 0.5	23	7	45	3.33	< 10	< 1	0.16	20	1.36	1980	< 1
23210	201 238	1.00	0.6	15	80	0.5	< 2	2.18	< 0.5	23	9	49	4.12	< 10	< 1	0.26	20	1.56	2160	< 1
23211	201 238	0.43	0.4	15	50	< 0.5	< 2	5.38	< 0.5	17	6	37	2.63	< 10	< 1	0.14	< 10	3.20	1660	< 1
23212	201 238	0.89	0.6	30	80	< 0.5	< 2	1.97	< 0.5	17	10	49	5.13	< 10	< 1	0.26	20	1.45	3630	< 1
23213	201 238	1.29	0.2	15	60	< 0.5	< 2	0.73	< 0.5	16	12	42	4.00	< 10	< 1	0.16	20	0.77	1015	< 1
23214	203 238	1.07	0.8	20	90	< 0.5	2	1.98	0.5	19	67	71	4.23	< 10	< 1	0.48	20	1.39	2140	1
23215	201 238	1.69	0.6	25	100	< 0.5	< 2	0.76	< 0.5	23	23	65	4.59	< 10	< 1	0.22	30	2.00	2080	1
23216	201 238	1.16	0.4	35	120	< 0.5	< 2	2.49	< 0.5	16	19	50	4.51	< 10	< 1	0.08	10	2.01	2430	< 1
23217	201 238	0.99	0.4	35	150	0.5	2	0.81	< 0.5	15	17	38	5.15	< 10	< 1	0.07	20	0.48	3010	< 1
23218	201 238	1.26	0.2	25	110	< 0.5	< 2	0.72	< 0.5	18	20	24	4.83	< 10	< 1	0.14	20	0.64	1440	< 1
23219	201 238	1.27	0.2	30	130	< 0.5	< 2	0.69	< 0.5	15	19	15	4.25	< 10	< 1	0.11	20	0.53	1480	< 1
23220	201 238	1.03	0.2	< 5	90	< 0.5	< 2	0.42	< 0.5	20	15	18	4.07	< 10	< 1	0.21	40	0.46	1395	< 1
23221	201 238	0.83	0.6	20	80	< 0.5	< 2	2.37	< 0.5	25	12	24	4.01	< 10	< 1	0.24	30	1.57	1965	< 1
23222	201 238	0.55	0.4	20	50	< 0.5	< 2	2.39	< 0.5	17	8	21	3.19	< 10	< 1	0.15	20	1.43	1440	< 1
23223	203 238	1.38	0.4	20	150	< 0.5	< 2	1.16	< 0.5	22	45	44	5.06	< 10	< 1	0.41	30	0.95	2290	1
23224	201 238	0.77	1.0	70	150	< 0.5	< 2	1.71	< 0.5	49	13	48	7.59	< 10	< 1	0.10	20	1.06	4680	2
23225	201 238	1.18	0.6	25	160	< 0.5	< 2	2.64	< 0.5	38	17	23	5.15	< 10	2	0.17	10	2.31	2340	1
23226	201 238	1.64	0.4	35	180	< 0.5	< 2	0.42	< 0.5	43	28	22	6.28	< 10	< 1	0.08	30	0.40	2670	1
23227	217 238	0.79	0.2	20	160	< 0.5	< 2	0.19	0.5	16	53	13	2.50	< 10	< 1	0.21	20	0.13	2660	< 1
23228	201 238	0.51	0.8	30	110	< 0.5	< 2	6.22	1.0	24	10	34	5.11	< 10	< 1	0.05	< 10	3.91	4150	1
23229	201 238	0.98	1.0	35	200	< 0.5	< 2	2.55	1.0	29	18	38	6.74	< 10	< 1	0.06	10	1.60	5590	1
23230	201 238	1.26	0.4	15	110	< 0.5	< 2	2.07	< 0.5	19	15	24	4.79	< 10	< 1	0.32	20	1.88	2320	< 1
23231	201 238	1.34	0.4	25	110	< 0.5	< 2	0.24	< 0.5	27	20	26	4.56	< 10	< 1	0.26	30	0.65	1690	< 1
23232	201 238	1.18	0.4	25	100	< 0.5	< 2	0.40	< 0.5	18	18	26	4.63	< 10	< 1	0.23	30	0.70	1570	< 1
23233	201 238	1.06	0.6	55	90	< 0.5	< 2	0.32	< 0.5	17	14	20	4.85	< 10	< 1	0.26	30	0.60	2050	< 1
23234	201 238	1.11	0.4	35	120	< 0.5	< 2	0.50	< 0.5	18	17	23	5.36	< 10	< 1	0.17	30	0.61	2680	< 1
23235	201 238	1.00	0.6	40	130	< 0.5	< 2	0.56	< 0.5	18	16	27	6.15	< 10	< 1	0.09	30	0.40	3240	< 1
23236	201 238	0.96	0.2	35	100	< 0.5	< 2	0.70	< 0.5	13	14	19	4.38	< 10	< 1	0.14	30	0.43	1930	< 1
23237	201 238	1.64	0.6	20	100	< 0.5	< 2	0.38	< 0.5	28	23	77	5.42	< 10	< 1	0.17	20	1.74	2780	< 1
23238	201 238	1.84	0.6	30	110	< 0.5	< 2	0.50	< 0.5	23	26	60	5.13	< 10	< 1	0.22	20	1.82	2520	1
23239	201 238	1.23	0.8	35	100	< 0.5	< 2	0.45	< 0.5	20	15	54	4.75	< 10	< 1	0.40	30	0.62	2220	< 1
23240	201 238	1.64	1.4	35	120	< 0.5	< 2	0.79	< 0.5	16	18	31	5.13	< 10	< 1	0.26	20	0.96	2060	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments :

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23201	201 238	0.01	25	1170	18	< 5	5	22	0.07	< 10	< 10	37	< 10	128
23202	201 238	0.01	23	960	24	< 5	8	12	0.02	< 10	< 10	22	< 10	232
23203	201 238	0.01	21	1410	16	< 5	5	14	0.02	< 10	< 10	29	< 10	252
23204	201 238	0.01	16	940	20	< 5	5	9	0.01	< 10	< 10	19	< 10	268
23205	201 238	0.01	17	970	18	< 5	6	9	0.02	< 10	< 10	20	< 10	428
23206	201 238	0.01	28	990	10	< 5	7	17	0.03	< 10	< 10	23	< 10	148
23207	201 238	0.01	27	860	16	< 5	5	14	0.02	< 10	< 10	22	< 10	146
23208	201 238	0.01	16	810	56	5	5	18	0.01	< 10	< 10	10	< 10	144
23209	201 238	0.01	25	750	82	5	5	14	0.01	< 10	< 10	12	< 10	216
23210	201 238	0.01	23	1110	54	5	7	17	0.07	< 10	< 10	39	< 10	206
23211	201 238	0.01	16	730	36	5	4	20	0.02	< 10	< 10	13	< 10	198
23212	201 238	0.01	24	880	50	< 5	7	15	0.03	< 10	< 10	18	< 10	226
23213	201 238	0.02	21	860	28	< 5	6	12	0.06	< 10	< 10	50	< 10	214
23214	203 238	0.02	27	840	94	< 5	6	15	0.02	< 10	< 10	23	< 10	292
23215	201 238	0.01	30	810	44	< 5	8	11	0.04	< 10	< 10	35	< 10	226
23216	201 238	0.01	27	660	34	< 5	7	14	0.04	< 10	< 10	32	< 10	292
23217	201 238	0.01	20	910	34	< 5	6	10	0.03	< 10	< 10	28	< 10	436
23218	201 238	0.01	32	1710	16	< 5	9	12	0.02	< 10	< 10	35	< 10	176
23219	201 238	0.01	22	1290	20	< 5	6	13	0.02	< 10	< 10	34	< 10	166
23220	201 238	0.01	24	960	16	< 5	8	11	0.02	< 10	< 10	26	< 10	106
23221	201 238	0.01	28	1270	14	5	8	31	0.02	< 10	< 10	21	< 10	118
23222	201 238	0.01	18	850	12	< 5	6	16	0.01	< 10	< 10	11	< 10	76
23223	203 238	0.01	32	1170	68	5	9	14	0.03	< 10	< 10	28	< 10	256
23224	201 238	0.01	67	1510	78	5	10	22	0.01	< 10	< 10	30	< 10	300
23225	201 238	0.01	54	1500	24	5	8	36	0.03	< 10	< 10	29	< 10	176
23226	201 238	0.01	47	1990	10	< 5	7	16	0.02	< 10	< 10	54	< 10	198
23227	217 238	0.01	11	780	18	< 5	1	6	0.02	< 10	< 10	39	< 10	134
23228	201 238	0.01	29	790	88	5	6	24	0.02	< 10	< 10	23	< 10	454
23229	201 238	0.01	37	980	60	5	7	16	0.03	< 10	< 10	36	< 10	528
23230	201 238	0.01	24	940	10	5	7	14	0.03	< 10	< 10	21	< 10	248
23231	201 238	0.01	31	680	18	< 5	7	11	0.06	< 10	< 10	33	< 10	168
23232	201 238	0.01	29	590	16	< 5	7	10	0.05	< 10	< 10	28	< 10	144
23233	201 238	0.01	27	630	14	5	7	7	0.04	< 10	< 10	22	< 10	142
23234	201 238	0.01	29	680	18	< 5	7	10	0.04	< 10	< 10	29	< 10	186
23235	201 238	0.01	28	860	24	5	7	9	0.02	< 10	< 10	29	< 10	292
23236	201 238	0.01	20	1060	24	< 5	5	9	0.02	< 10	< 10	23	< 10	216
23237	201 238	0.01	35	710	70	5	9	9	0.03	< 10	< 10	38	< 10	302
23238	201 238	0.01	31	670	52	5	8	9	0.03	< 10	< 10	40	< 10	288
23239	201 238	0.01	21	720	76	5	8	7	0.04	< 10	< 10	30	< 10	330
23240	201 238	0.01	17	1030	382	5	7	10	0.06	< 10	< 10	43	< 10	466

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23241	201 238	2.34	0.4	35	110	< 0.5	< 2	0.48	< 0.5	19	23	44	4.67	< 10	< 1	0.63	30	1.69	1750	1
23242	201 238	1.45	0.2	15	80	< 0.5	< 2	0.77	0.5	19	15	45	4.76	< 10	< 1	0.25	30	1.21	1820	< 1
23243	201 238	1.61	0.2	25	80	< 0.5	< 2	0.82	< 0.5	22	15	49	4.79	< 10	< 1	0.26	30	1.37	1660	< 1
23244	201 238	0.85	0.8	25	90	< 0.5	< 2	0.96	0.5	17	13	49	4.48	< 10	< 1	0.15	30	0.72	2390	< 1
23245	201 238	1.54	0.4	20	110	< 0.5	< 2	0.84	< 0.5	14	20	23	3.56	< 10	1	0.32	20	1.17	1200	< 1
23246	201 238	0.81	0.4	40	120	< 0.5	< 2	1.09	1.0	19	12	29	4.80	< 10	< 1	0.10	20	0.54	3720	< 1
23247	201 238	0.88	< 0.2	20	100	< 0.5	< 2	1.38	< 0.5	18	10	63	4.54	< 10	< 1	0.26	20	0.97	2400	< 1
23248	201 238	0.67	< 0.2	40	130	< 0.5	< 2	1.94	< 0.5	16	9	113	6.96	< 10	< 1	0.12	20	0.76	4600	< 1
23249	201 238	0.77	0.4	25	90	< 0.5	< 2	2.23	< 0.5	18	12	56	3.20	< 10	< 1	0.17	20	1.38	1325	< 1
23250	201 238	0.71	0.2	20	60	< 0.5	< 2	0.80	< 0.5	13	10	37	3.62	< 10	< 1	0.12	30	0.43	1010	1
23251	201 238	0.97	0.2	25	100	< 0.5	< 2	1.08	< 0.5	12	15	38	5.51	< 10	< 1	0.13	30	0.54	2390	1
23252	201 238	0.53	0.2	20	80	< 0.5	< 2	2.70	< 0.5	16	9	35	3.29	< 10	< 1	0.10	20	1.57	1940	1
23280	201 238	1.00	0.2	25	100	< 0.5	< 2	1.07	< 0.5	17	14	50	4.45	< 10	< 1	0.14	20	0.77	1580	1
23281	203 238	0.71	0.2	5	70	0.5	< 2	2.05	< 0.5	8	18	36	2.34	< 10	< 1	0.20	10	0.57	1100	< 1
23282	201 238	1.41	0.2	20	150	< 0.5	< 2	0.67	< 0.5	17	20	29	4.10	< 10	< 1	0.11	20	0.63	1420	< 1
23283	201 238	0.78	0.4	30	100	< 0.5	< 2	1.10	< 0.5	17	9	34	5.06	< 10	< 1	0.15	20	0.55	1940	1
23284	201 238	1.11	0.4	15	80	< 0.5	< 2	1.24	< 0.5	15	11	38	3.97	< 10	< 1	0.29	20	0.93	1400	< 1
23285	201 238	0.85	0.2	15	80	< 0.5	< 2	2.00	< 0.5	17	16	46	3.57	< 10	< 1	0.18	20	1.32	1350	1
23286	201 238	1.07	0.6	15	120	< 0.5	< 2	2.31	0.5	17	14	61	4.88	< 10	< 1	0.20	20	1.53	2020	< 1
23287	201 238	1.81	0.6	25	130	0.5	< 2	1.15	< 0.5	23	23	64	4.39	< 10	< 1	0.43	30	1.47	1555	1
23288	201 238	0.66	0.8	15	110	< 0.5	< 2	7.54	0.5	15	9	13	2.90	< 10	< 1	0.11	< 10	4.62	2220	< 1
23289	201 238	0.68	0.2	30	110	< 0.5	< 2	5.05	1.0	24	10	14	3.36	< 10	< 1	0.10	< 10	2.99	2350	< 1
23290	201 238	1.83	0.4	60	110	< 0.5	< 2	0.71	< 0.5	37	21	44	5.68	10	< 1	0.14	40	0.99	1355	1
23291	201 238	1.14	0.6	45	80	< 0.5	< 2	3.25	0.5	28	13	47	4.05	< 10	< 1	0.10	10	2.33	1255	< 1
23292	201 238	0.94	0.2	35	90	< 0.5	< 2	1.36	0.5	22	14	46	4.06	< 10	< 1	0.11	20	1.02	1445	1
23293	201 238	1.29	0.2	55	110	< 0.5	< 2	0.77	< 0.5	28	16	49	4.91	< 10	< 1	0.14	30	0.87	1765	< 1
23294	201 238	1.12	0.4	40	100	< 0.5	< 2	2.14	< 0.5	24	16	42	4.15	< 10	< 1	0.17	20	1.64	1490	< 1
23295	201 238	1.30	0.8	45	230	< 0.5	< 2	1.80	< 0.5	17	20	33	5.42	< 10	< 1	0.08	20	1.34	2670	1
23296	201 238	0.81	0.4	35	110	< 0.5	< 2	4.05	< 0.5	16	13	25	4.91	< 10	< 1	0.06	< 10	2.46	2900	1
23297	201 238	0.72	< 0.2	65	110	< 0.5	< 2	4.30	< 0.5	17	13	23	5.16	< 10	< 1	0.05	< 10	2.58	2950	1
23298	201 238	1.00	< 0.2	65	130	< 0.5	< 2	1.31	< 0.5	20	16	27	5.88	< 10	< 1	0.07	20	0.85	3120	< 1
23299	201 238	0.65	< 0.2	80	110	< 0.5	< 2	3.20	< 0.5	20	9	26	5.77	< 10	< 1	0.05	< 10	1.83	3230	1
23300	201 238	0.36	0.4	80	70	< 0.5	< 2	6.48	< 0.5	18	5	19	4.90	< 10	< 1	0.03	< 10	3.78	2370	1
23301	201 238	0.77	< 0.2	55	160	< 0.5	< 2	2.76	< 0.5	23	9	37	6.62	< 10	< 1	0.08	10	1.48	5250	< 1
23302	201 238	0.73	< 0.2	30	150	< 0.5	< 2	6.43	0.5	17	13	21	5.32	< 10	< 1	0.04	< 10	3.82	4670	< 1
23303	201 238	0.59	< 0.2	70	90	< 0.5	< 2	5.70	< 0.5	24	11	30	5.60	< 10	2	0.03	< 10	3.34	2880	2
23304	201 238	0.68	< 0.2	20	120	< 0.5	< 2	7.81	< 0.5	22	12	24	4.30	< 10	< 1	0.03	< 10	4.61	3650	< 1
23305	201 238	0.62	1.0	15	110	< 0.5	< 2	5.49	2.0	14	10	27	8.25	< 10	< 1	0.04	< 10	2.74	8700	< 1
23306	201 238	0.42	1.2	20	100	< 0.5	< 2	10.85	1.0	24	9	34	5.97	< 10	< 1	0.04	< 10	6.15	5500	1
23307	201 238	0.67	1.6	35	180	< 0.5	< 2	7.36	0.5	22	12	36	6.62	< 10	< 1	0.03	< 10	4.17	6210	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date :16-JUL-89
Invoice # :I-8919848
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23241	201	238	0.01	28	670	608	< 5	8	9	0.08	< 10	< 10	42	< 10	588
23242	201	238	0.01	20	790	530	< 5	7	10	0.10	< 10	< 10	46	< 10	380
23243	201	238	0.01	22	1050	438	< 5	8	12	0.16	< 10	< 10	62	< 10	492
23244	201	238	0.01	22	780	352	5	6	11	0.03	< 10	< 10	22	< 10	554
23245	201	238	0.01	24	860	50	< 5	5	12	0.04	< 10	< 10	26	< 10	130
23246	201	238	0.01	23	950	190	< 5	5	12	0.02	< 10	< 10	19	< 10	886
23247	201	238	0.01	29	1160	36	< 5	5	13	0.01	< 10	< 10	15	< 10	114
23248	201	238	0.01	21	1630	84	5	7	18	0.01	< 10	< 10	16	< 10	236
23249	201	238	0.01	24	900	34	5	5	17	0.04	< 10	< 10	22	< 10	358
23250	201	238	0.01	17	640	40	< 5	5	9	0.02	< 10	< 10	20	< 10	632
23251	201	238	0.01	20	1170	46	< 5	6	12	0.02	< 10	< 10	25	< 10	390
23252	201	238	0.01	19	700	54	< 5	5	17	0.02	< 10	< 10	18	< 10	250
23280	201	238	0.01	27	840	64	< 5	7	11	0.03	< 10	< 10	28	< 10	396
23281	203	238	0.01	15	1050	30	< 5	3	13	0.01	< 10	< 10	14	< 10	120
23282	201	238	0.01	24	700	54	< 5	6	13	0.04	< 10	< 10	36	< 10	288
23283	201	238	< 0.01	21	1100	58	< 5	5	9	0.01	< 10	< 10	16	< 10	162
23284	201	238	0.01	24	970	84	5	5	10	0.02	< 10	< 10	18	< 10	284
23285	201	238	0.01	25	910	54	< 5	5	15	0.03	< 10	< 10	25	< 10	364
23286	201	238	0.01	23	860	428	< 5	5	13	0.03	< 10	< 10	27	< 10	856
23287	201	238	0.01	33	870	64	< 5	6	11	0.04	< 10	< 10	32	< 10	356
23288	201	238	0.01	17	510	18	5	4	14	0.02	< 10	< 10	20	< 10	756
23289	201	238	0.01	20	730	20	< 5	4	12	0.02	< 10	< 10	19	< 10	812
23290	201	238	0.01	37	950	58	< 5	9	14	0.06	< 10	< 10	80	< 10	614
23291	201	238	0.01	35	900	46	5	6	15	0.04	< 10	< 10	48	< 10	896
23292	201	238	0.01	30	810	52	< 5	6	10	0.03	< 10	< 10	34	< 10	498
23293	201	238	0.01	34	880	46	5	7	10	0.04	< 10	< 10	50	< 10	610
23294	201	238	0.01	31	790	52	5	6	12	0.03	< 10	< 10	38	< 10	462
23295	201	238	0.01	28	710	34	5	7	13	0.04	< 10	< 10	39	< 10	468
23296	201	238	0.01	26	690	20	5	5	10	0.02	< 10	< 10	26	< 10	356
23297	201	238	0.01	34	580	44	5	5	9	0.02	< 10	< 10	24	< 10	288
23298	201	238	0.01	38	750	28	5	6	9	0.03	< 10	< 10	33	< 10	304
23299	201	238	0.01	41	670	38	10	5	8	0.02	< 10	< 10	23	< 10	370
23300	201	238	0.01	30	560	30	10	4	11	0.01	< 10	< 10	13	< 10	156
23301	201	238	0.01	34	950	48	5	6	10	0.02	< 10	< 10	27	< 10	572
23302	201	238	0.01	22	550	12	5	7	14	0.03	< 10	< 10	32	< 10	738
23303	201	238	0.01	35	480	34	10	5	13	0.03	< 10	< 10	27	< 10	604
23304	201	238	0.01	22	540	4	< 5	6	17	0.03	< 10	< 10	28	< 10	298
23305	201	238	0.01	21	1040	14	5	5	16	0.02	< 10	< 10	28	< 10	878
23306	201	238	0.01	23	770	114	5	5	33	0.01	< 10	< 10	30	< 10	456
23307	201	238	0.01	24	920	84	5	5	20	0.01	< 10	< 10	31	< 10	452

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 3-A
Tot. Pages: 9
Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23308	201 238	0.86	0.4	10	150	< 0.5	< 2	3.23	1.0	16	11	25	5.91	10	< 1	0.06	10	1.77	4390	< 1
23309	201 238	0.59	0.2	< 5	100	< 0.5	< 2	2.88	0.5	12	10	23	4.51	< 10	< 1	0.05	10	1.54	3520	< 1
23310	201 238	0.71	0.2	10	100	< 0.5	< 2	0.92	0.5	16	11	21	4.43	10	< 1	0.07	20	0.42	2620	< 1
23311	201 238	0.51	0.8	50	80	< 0.5	< 2	4.27	< 0.5	19	10	24	5.70	< 10	< 1	0.05	< 10	2.50	2390	< 1
23312	201 238	0.97	0.4	15	140	< 0.5	< 2	1.55	1.0	19	17	25	5.35	10	< 1	0.06	20	0.89	3330	< 1
23313	201 238	0.81	0.4	< 5	120	< 0.5	< 2	4.37	1.5	15	14	24	4.70	< 10	1	0.07	< 10	2.51	3130	< 1
23314	201 238	1.23	< 0.2	20	180	< 0.5	< 2	2.88	0.5	15	21	27	5.28	10	1	0.08	10	1.84	3460	< 1
23315	201 238	0.86	< 0.2	< 5	100	< 0.5	< 2	4.72	1.5	14	14	26	4.86	< 10	1	0.07	< 10	2.75	2410	< 1
23316	201 238	0.95	0.4	< 5	120	< 0.5	< 2	4.15	1.5	17	17	32	5.12	< 10	< 1	0.10	< 10	2.54	2920	< 1
23317	201 238	1.64	0.2	35	150	< 0.5	2	0.75	< 0.5	25	24	44	5.46	10	1	0.16	20	0.86	2290	< 1
23318	201 238	1.50	0.2	25	160	< 0.5	< 2	0.96	0.5	25	23	51	5.23	20	< 1	0.17	30	0.92	2210	< 1
23319	201 238	1.49	0.2	10	130	< 0.5	< 2	0.68	0.5	24	20	50	4.99	20	1	0.17	30	0.82	1960	< 1
23359	201 238	0.88	0.2	5	120	< 0.5	< 2	1.13	< 0.5	16	13	31	5.78	10	1	0.15	30	0.64	2850	< 1
23360	201 238	0.58	0.2	5	100	< 0.5	< 2	8.29	< 0.5	9	12	20	3.43	< 10	< 1	0.05	< 10	4.97	2350	< 1
23361	201 238	0.17	0.2	< 5	70	< 0.5	< 2	13.15	< 0.5	1	7	10	2.46	< 10	< 1	0.02	< 10	7.67	2520	< 1
23362	201 238	0.41	0.4	10	50	< 0.5	< 2	8.56	< 0.5	11	10	23	2.66	< 10	< 1	0.04	< 10	5.10	1705	< 1
23363	201 238	0.31	0.4	< 5	50	< 0.5	< 2	10.50	0.5	7	9	24	2.34	< 10	< 1	0.04	< 10	6.26	1660	< 1
23364	201 238	0.19	0.2	< 5	30	< 0.5	< 2	11.65	0.5	1	4	11	1.94	< 10	< 1	0.02	< 10	6.95	1745	< 1
23365	201 238	0.37	0.6	< 5	50	< 0.5	< 2	6.31	1.0	12	10	29	2.60	< 10	< 1	0.07	< 10	3.73	1905	< 1
23366	201 238	0.31	0.6	< 5	50	< 0.5	< 2	8.57	1.0	10	9	23	2.31	< 10	< 1	0.05	< 10	5.07	1510	< 1
23367	201 238	0.74	0.8	15	100	< 0.5	< 2	1.38	1.5	20	8	43	4.05	10	1	0.07	20	0.85	2580	< 1
23368	201 238	0.26	0.2	15	50	< 0.5	< 2	8.93	< 0.5	12	5	17	2.54	< 10	< 1	0.04	< 10	5.18	1745	< 1
23369	201 238	0.38	0.4	< 5	50	< 0.5	< 2	6.66	1.0	13	4	23	2.33	< 10	< 1	0.05	< 10	3.95	1255	< 1
23370	201 238	0.56	0.6	< 5	30	< 0.5	6	3.61	0.5	23	10	26	3.04	< 10	< 1	0.07	< 10	2.05	950	< 1
23371	201 238	0.47	0.2	5	60	< 0.5	< 2	5.63	0.5	12	6	20	2.59	< 10	1	0.05	< 10	3.27	1415	< 1
23372	201 238	0.47	0.2	10	60	< 0.5	< 2	5.00	0.5	18	6	24	2.89	< 10	< 1	0.07	< 10	2.93	2100	< 1
23373	201 238	0.48	0.4	5	60	< 0.5	< 2	4.92	1.0	18	9	25	3.01	< 10	< 1	0.06	< 10	2.83	2010	< 1
23374	201 238	0.47	0.8	5	60	< 0.5	< 2	5.60	0.5	13	6	27	3.23	< 10	< 1	0.06	< 10	3.36	2750	< 1
23375	201 238	1.27	0.4	10	80	< 0.5	< 2	3.20	< 0.5	13	31	58	3.50	10	1	0.08	10	2.54	1260	1
23376	201 238	1.20	< 0.2	15	40	< 0.5	< 2	6.67	< 0.5	12	25	59	3.07	< 10	< 1	0.08	< 10	3.31	1480	< 1
23377	201 238	1.33	< 0.2	< 5	180	< 0.5	< 2	1.16	0.5	13	25	34	6.40	10	< 1	0.06	20	0.69	6850	2
23378	203 238	1.93	< 0.2	25	150	< 0.5	< 2	0.67	< 0.5	19	98	43	5.99	10	1	0.17	20	1.27	3880	2
23379	203 238	0.79	0.4	65	50	< 0.5	< 2	1.18	< 0.5	56	51	112	6.91	10	1	0.17	20	0.43	3510	7
23380	201 238	2.46	< 0.2	70	110	< 0.5	< 2	0.15	< 0.5	21	52	108	7.75	10	< 1	0.09	20	1.26	3460	1
23381	201 238	2.60	< 0.2	< 5	120	< 0.5	< 2	0.34	< 0.5	12	36	52	4.42	10	< 1	0.08	20	2.04	1835	1
23382	201 238	2.19	< 0.2	5	140	< 0.5	< 2	0.25	0.5	13	32	45	5.11	10	1	0.07	20	1.14	2710	2
23383	201 238	2.35	< 0.2	< 5	70	< 0.5	< 2	0.55	0.5	12	39	42	4.62	10	1	0.10	30	2.51	1575	< 1
23426	201 238	1.20	1.0	25	80	< 0.5	< 2	0.49	0.5	12	20	49	3.92	10	< 1	0.07	20	0.61	1030	1
23427	201 238	0.41	1.2	5	50	< 0.5	< 2	6.79	1.5	9	3	29	2.70	< 10	< 1	0.07	< 10	4.69	2330	< 1
23428	201 238	1.23	1.6	30	60	< 0.5	< 2	2.60	1.5	21	19	94	4.07	10	< 1	0.10	20	2.37	1755	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23308	201 238	0.01	26	1070	98	5	6	13	0.02	20	< 10	30	< 10	348
23309	201 238	0.01	19	920	64	5	5	10	0.01	10	< 10	19	< 10	282
23310	201 238	0.01	25	860	48	5	5	8	0.01	10	< 10	22	< 10	200
23311	201 238	0.01	33	630	56	10	4	10	0.01	20	< 10	17	< 10	178
23312	201 238	0.01	29	920	62	5	6	10	0.02	10	< 10	29	< 10	236
23313	201 238	0.01	24	820	36	5	5	13	0.02	10	< 10	26	< 10	376
23314	201 238	0.01	28	730	24	5	6	14	0.04	10	< 10	37	< 10	390
23315	201 238	0.01	27	770	34	5	5	14	0.03	10	< 10	26	< 10	366
23316	201 238	0.01	30	810	26	5	6	16	0.04	20	< 10	29	< 10	324
23317	201 238	0.01	33	840	60	5	8	13	0.06	10	< 10	52	< 10	362
23318	201 238	0.02	35	850	48	5	8	13	0.05	10	< 10	48	< 10	404
23319	201 238	0.01	36	700	48	5	8	12	0.05	10	< 10	51	< 10	346
23359	201 238	0.01	73	890	30	5	12	11	0.02	10	< 10	24	< 10	94
23360	201 238	0.02	17	510	60	5	6	16	0.02	< 10	< 10	21	< 10	120
23361	201 238	0.01	10	100	58	5	4	54	< 0.01	< 10	< 10	16	< 10	302
23362	201 238	0.01	17	580	84	5	4	31	0.01	< 10	< 10	16	< 10	368
23363	201 238	0.01	12	280	176	5	4	25	0.01	10	< 10	13	< 10	358
23364	201 238	0.01	8	270	42	5	4	29	< 0.01	< 10	< 10	9	< 10	180
23365	201 238	0.01	15	680	318	5	6	22	0.01	10	< 10	13	< 10	492
23366	201 238	0.01	15	470	236	5	4	29	0.01	10	< 10	14	< 10	596
23367	201 238	0.01	29	670	366	5	6	14	0.02	10	< 10	24	< 10	1030
23368	201 238	0.01	16	590	82	5	5	97	0.01	10	< 10	12	< 10	356
23369	201 238	0.01	18	680	150	< 5	5	54	0.02	10	< 10	15	< 10	598
23370	201 238	0.01	29	880	184	5	7	41	< 0.01	10	< 10	19	< 10	272
23371	201 238	0.01	16	680	108	5	5	42	0.02	10	< 10	17	< 10	324
23372	201 238	0.01	25	670	140	< 5	6	47	0.01	10	< 10	15	< 10	408
23373	201 238	0.01	23	820	200	5	5	46	0.01	20	< 10	16	< 10	606
23374	201 238	0.01	15	690	304	20	6	15	0.01	10	< 10	17	< 10	482
23375	201 238	0.01	32	770	84	5	5	27	0.07	< 10	< 10	48	< 10	292
23376	201 238	0.01	27	610	56	5	4	31	0.06	< 10	< 10	34	< 10	368
23377	201 238	0.01	27	1730	42	5	6	14	0.03	< 10	< 10	52	< 10	344
23378	203 238	0.01	37	910	46	10	8	12	0.04	< 10	< 10	78	< 10	250
23379	203 238	0.01	48	1330	48	20	8	16	0.01	< 10	< 10	39	< 10	106
23380	201 238	0.01	38	630	96	10	8	7	0.06	< 10	< 10	88	< 10	348
23381	201 238	0.01	28	470	102	5	6	10	0.09	< 10	< 10	60	< 10	508
23382	201 238	0.01	30	690	48	5	6	10	0.05	< 10	< 10	60	< 10	302
23383	201 238	0.01	30	410	36	5	8	9	0.07	< 10	< 10	49	< 10	750
23426	201 238	0.01	28	420	428	10	6	14	0.06	< 10	< 10	45	< 10	810
23427	201 238	0.01	14	460	414	5	4	18	0.01	< 10	< 10	12	< 10	938
23428	201 238	0.01	34	620	630	< 5	7	12	0.03	< 10	< 10	48	< 10	1740

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23429	201	238	0.50	2.4	15	50	0.5	< 2	10.10	6.0	13	8	32	3.31	< 10	1	0.07	< 10	5.82	2640	< 1
23430	201	238	0.34	1.8	10	40	0.5	< 2	10.60	3.0	1	5	24	2.19	< 10	1	0.03	< 10	6.25	1765	< 1
23431	201	238	0.61	1.2	15	90	< 0.5	< 2	4.47	1.5	10	9	28	3.62	< 10	1	0.07	< 10	2.56	2610	< 1
23432	201	238	0.63	1.2	15	80	< 0.5	< 2	2.12	2.0	15	11	35	4.79	10	< 1	0.12	30	1.11	2700	< 1
23433	201	238	0.35	0.6	15	70	< 0.5	< 2	4.86	0.5	10	10	37	3.73	< 10	< 1	0.06	< 10	2.74	2670	< 1
23434	201	238	0.42	0.4	20	80	< 0.5	2	1.17	< 0.5	14	8	20	2.92	10	< 1	0.10	20	0.67	1960	< 1
23435	201	238	0.49	0.4	< 5	100	< 0.5	< 2	5.94	0.5	6	11	20	3.21	< 10	< 1	0.08	< 10	3.58	2350	< 1
23436	217	238	1.85	0.8	25	90	< 0.5	2	0.12	0.5	26	40	43	4.68	10	< 1	0.79	30	1.17	1175	< 1
23437	217	238	2.28	< 0.2	10	70	< 0.5	< 2	0.55	< 0.5	7	40	5	4.04	10	< 1	0.67	40	2.21	1425	< 1
23438	201	238	1.39	1.2	< 5	70	< 0.5	< 2	2.41	1.0	9	17	25	3.97	10	< 1	0.23	20	2.54	2100	< 1
23439	201	238	1.46	1.6	< 5	90	< 0.5	2	0.35	1.0	13	18	49	4.55	10	< 1	0.17	30	1.51	2180	< 1
23440	217	238	1.31	0.2	< 5	70	< 0.5	< 2	0.14	1.0	10	22	15	3.47	10	< 1	0.49	40	1.05	1655	< 1
23441	201	238	0.98	0.4	< 5	80	< 0.5	< 2	1.19	0.5	15	11	31	4.96	10	< 1	0.16	30	1.29	2780	< 1
23442	201	238	0.65	0.4	5	90	< 0.5	2	1.12	0.5	9	12	29	3.79	10	< 1	0.11	30	0.84	1860	< 1
23443	201	238	0.71	0.4	5	80	< 0.5	< 2	0.50	0.5	8	10	37	3.53	10	< 1	0.13	30	0.34	1215	< 1
23444	201	238	0.54	0.8	5	90	< 0.5	< 2	3.96	0.5	17	11	54	3.67	10	< 1	0.09	10	2.24	1770	< 1
23445	203	238	0.66	0.6	< 5	90	< 0.5	< 2	2.75	1.0	15	35	43	3.84	10	< 1	0.29	30	1.39	2380	< 1
23446	201	238	0.74	1.2	20	90	< 0.5	< 2	1.34	1.0	15	10	34	4.34	10	1	0.10	30	0.58	2500	< 1
23447	201	238	0.57	1.6	15	90	< 0.5	< 2	4.54	1.5	12	13	30	3.51	< 10	< 1	0.08	< 10	2.33	2800	< 1
23448	201	238	0.88	1.6	25	90	< 0.5	< 2	4.38	3.0	12	16	56	4.20	< 10	< 1	0.08	< 10	2.55	3100	< 1
23449	201	238	0.29	0.2	25	50	< 0.5	< 2	11.40	0.5	2	5	15	2.23	< 10	< 1	0.04	< 10	6.55	2420	< 1
23450	201	238	1.04	0.8	20	70	< 0.5	< 2	8.79	1.5	16	20	65	4.44	< 10	< 1	0.10	< 10	5.75	3600	1
23451	201	238	1.06	0.8	15	60	< 0.5	< 2	6.07	0.5	18	17	61	3.70	< 10	< 1	0.07	< 10	4.08	1800	< 1
23452	201	238	0.96	2.0	35	90	< 0.5	< 2	5.44	2.0	16	16	57	3.97	< 10	< 1	0.07	< 10	3.48	2870	< 1
23453	201	238	0.74	2.2	< 5	60	< 0.5	< 2	7.47	2.5	10	12	38	3.55	< 10	< 1	0.04	< 10	4.63	2620	< 1
23454	201	238	1.59	0.8	45	130	0.5	< 2	0.57	0.5	12	25	36	4.60	20	1	0.07	30	0.64	1770	1
23455	201	238	1.07	0.6	20	120	1.0	< 2	1.43	0.5	11	18	33	4.96	10	< 1	0.07	20	0.57	3310	< 1
23456	201	238	2.56	0.2	20	180	< 0.5	< 2	0.62	< 0.5	14	52	35	5.81	20	< 1	0.07	20	1.05	2520	1
23457	201	238	1.83	0.4	35	170	1.0	< 2	0.52	< 0.5	11	27	27	5.38	10	< 1	0.07	20	0.65	2430	1
23458	201	238	1.74	< 0.2	55	160	1.0	< 2	0.94	< 0.5	19	33	55	7.43	20	< 1	0.07	30	1.10	6160	2
23459	201	238	2.39	< 0.2	55	170	1.0	< 2	0.61	< 0.5	14	38	32	6.06	20	1	0.08	20	1.23	3080	2
23460	201	238	1.89	< 0.2	50	200	< 0.5	< 2	0.60	< 0.5	16	42	32	6.85	20	1	0.08	20	0.78	4050	1
23461	201	238	1.83	0.2	55	130	< 0.5	< 2	0.92	< 0.5	19	43	51	5.43	20	< 1	0.11	30	1.34	2380	1
23462	201	238	2.94	< 0.2	55	160	< 0.5	< 2	0.22	< 0.5	22	47	51	5.51	20	< 1	0.07	20	1.00	1450	1
23463	201	238	1.88	< 0.2	45	90	< 0.5	< 2	0.31	< 0.5	62	25	68	9.80	20	1	0.09	20	0.59	4750	< 1
23464	201	238	2.69	< 0.2	65	180	< 0.5	< 2	0.43	< 0.5	42	64	126	10.50	20	4	0.06	20	1.64	5420	1
23491	201	238	0.58	< 0.2	< 5	90	< 0.5	< 2	3.46	< 0.5	16	11	25	5.44	10	< 1	0.13	20	2.38	2420	< 1
23492	201	238	0.99	< 0.2	20	90	< 0.5	< 2	3.06	< 0.5	12	16	18	5.50	10	1	0.12	30	2.30	2450	< 1
23493	201	238	0.61	0.6	20	80	< 0.5	< 2	9.95	< 0.5	8	13	33	3.04	< 10	< 1	0.05	< 10	6.40	1505	< 1
23494	201	238	0.39	0.8	< 5	50	< 0.5	< 2	11.35	< 0.5	6	11	23	2.55	< 10	< 1	0.04	< 10	7.21	1235	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23429	201	238	0.01	16	420	968	5	5	18	0.02	< 10	< 10	16	< 10	4130
23430	201	238	0.01	8	320	802	5	4	14	0.01	10	< 10	13	< 10	2020
23431	201	238	0.01	17	700	754	5	6	17	0.01	< 10	< 10	20	< 10	962
23432	201	238	0.01	19	1070	514	5	7	16	0.01	10	< 10	17	< 10	1825
23433	201	238	0.01	14	550	184	10	8	22	0.01	10	< 10	10	< 10	396
23434	201	238	0.01	16	590	70	< 5	7	7	0.01	10	< 10	9	< 10	352
23435	201	238	0.01	10	480	74	10	5	10	0.01	10	< 10	13	< 10	218
23436	217	238	< 0.01	24	430	336	10	6	4	0.03	< 10	< 10	13	< 10	348
23437	217	238	0.01	23	380	48	5	7	4	0.02	< 10	< 10	14	< 10	122
23438	201	238	0.01	18	560	82	5	8	10	0.02	< 10	< 10	14	< 10	126
23439	201	238	0.01	22	640	134	5	9	6	0.02	< 10	< 10	14	< 10	298
23440	217	238	< 0.01	20	460	86	10	6	2	0.01	< 10	< 10	9	< 10	338
23441	201	238	0.01	18	560	162	< 5	8	6	0.02	< 10	< 10	13	< 10	258
23442	201	238	0.01	14	660	88	5	7	7	0.01	< 10	< 10	15	< 10	216
23443	201	238	0.01	16	880	100	5	7	6	0.01	< 10	< 10	14	< 10	210
23444	201	238	0.01	20	740	126	10	7	21	0.02	< 10	< 10	15	< 10	368
23445	203	238	0.01	19	870	146	5	7	21	0.01	< 10	< 10	14	< 10	436
23446	201	238	< 0.01	19	980	444	5	7	14	0.01	< 10	< 10	19	< 10	852
23447	201	238	0.01	18	820	710	5	6	17	0.01	< 10	< 10	17	< 10	1560
23448	201	238	0.01	19	690	858	10	7	13	0.02	< 10	< 10	30	< 10	2590
23449	201	238	0.01	8	560	226	5	4	16	< 0.01	< 10	< 10	10	< 10	442
23450	201	238	0.01	23	600	364	10	10	17	0.01	10	< 10	34	< 10	978
23451	201	238	0.01	27	670	368	10	7	18	0.03	< 10	< 10	34	< 10	774
23452	201	238	0.01	26	820	1110	10	8	14	0.02	< 10	< 10	30	< 10	1210
23453	201	238	0.01	20	660	2650	10	6	16	0.02	< 10	< 10	27	< 10	1160
23454	201	238	0.01	31	650	276	5	8	12	0.06	< 10	< 10	57	< 10	606
23455	201	238	0.01	18	1290	242	5	6	20	0.02	< 10	< 10	30	< 10	836
23456	201	238	0.01	37	1220	664	10	10	13	0.07	10	< 10	77	< 10	432
23457	201	238	< 0.01	26	1160	366	10	7	9	0.04	< 10	< 10	56	< 10	642
23458	201	238	< 0.01	39	1610	110	15	12	11	0.03	20	< 10	62	< 10	328
23459	201	238	0.01	32	1400	50	15	8	11	0.06	< 10	< 10	78	< 10	422
23460	201	238	0.01	33	1650	34	10	10	11	0.05	< 10	< 10	74	< 10	384
23461	201	238	0.01	41	1000	102	10	10	16	0.08	< 10	< 10	68	< 10	328
23462	201	238	0.01	43	570	38	10	8	10	0.08	< 10	< 10	80	< 10	122
23463	201	238	0.01	50	1880	32	15	14	12	0.03	< 10	< 10	72	20	134
23464	201	238	0.01	74	1090	38	15	24	18	0.05	< 10	< 10	85	30	360
23491	201	238	0.01	26	470	42	10	9	11	0.01	< 10	< 10	14	20	128
23492	201	238	0.01	22	990	40	10	9	10	0.02	10	< 10	23	20	230
23493	201	238	0.02	20	400	310	15	5	25	0.04	< 10	< 10	25	10	280
23494	201	238	0.01	15	200	192	10	4	33	0.01	< 10	< 10	16	< 10	286

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23495	201 238	0.28	2.2	10	40	0.5	< 2	10.75	< 0.5	11	7	38	2.71	< 10	< 1	0.04	< 10	6.94	1160	< 1
23496	201 238	0.30	1.6	10	50	0.5	< 2	9.66	0.5	10	6	35	2.75	< 10	< 1	0.03	< 10	6.21	1415	< 1
23497	201 238	0.33	1.0	< 5	70	0.5	< 2	9.05	0.5	11	5	42	2.87	< 10	< 1	0.04	< 10	5.81	1890	< 1
23498	201 238	0.99	1.6	5	90	< 0.5	< 2	1.75	2.0	40	17	74	5.13	< 10	< 1	0.22	30	1.35	1645	< 1
23499	201 238	0.84	0.8	5	80	< 0.5	4	2.83	2.0	18	15	31	4.18	< 10	< 1	0.13	20	1.96	2540	< 1
23500	201 238	1.67	1.0	10	130	< 0.5	< 2	1.53	1.0	21	26	70	5.62	10	< 1	0.12	20	1.97	3300	< 1
23501	201 238	1.46	1.2	15	100	< 0.5	< 2	3.39	2.0	20	22	95	4.67	< 10	< 1	0.12	10	3.06	2690	< 1
23502	201 238	1.55	1.4	5	110	< 0.5	< 2	1.89	1.5	17	21	52	5.31	< 10	< 1	0.09	20	2.13	2930	< 1
23503	201 238	1.23	1.0	15	80	< 0.5	< 2	2.91	1.0	24	21	92	4.87	< 10	< 1	0.10	10	2.47	2430	< 1
23504	201 238	1.06	0.8	< 5	270	< 0.5	< 2	1.68	3.5	16	15	70	8.27	< 10	< 1	0.06	20	0.92	7030	< 1
23505	201 238	0.98	0.6	20	110	< 0.5	< 2	0.65	1.5	13	21	35	5.21	< 10	< 1	0.03	20	0.42	3040	< 1
23506	201 238	1.22	0.6	< 5	140	< 0.5	< 2	0.57	7.5	16	25	45	5.14	< 10	< 1	0.05	20	0.47	3200	< 1
23507	201 238	1.20	0.4	25	120	< 0.5	< 2	0.69	< 0.5	11	22	32	5.80	10	< 1	0.06	20	0.42	2610	< 1
23508	201 238	1.04	0.6	55	130	< 0.5	< 2	1.90	0.5	19	22	34	5.42	10	< 1	0.06	20	1.26	3390	< 1
23509	201 238	2.70	< 0.2	10	130	< 0.5	< 2	0.64	< 0.5	26	113	53	6.24	20	< 1	0.08	10	1.85	2100	< 1
23510	201 238	2.14	0.2	20	80	< 0.5	< 2	0.61	< 0.5	25	66	70	6.04	10	< 1	0.08	20	1.65	2140	< 1
23511	201 238	1.79	0.2	20	70	< 0.5	< 2	2.26	< 0.5	23	55	87	5.93	10	< 1	0.09	20	2.61	2500	< 1
23512	201 238	1.21	0.4	35	60	< 0.5	< 2	2.60	< 0.5	27	33	76	5.64	10	< 1	0.08	20	2.32	3500	< 1
23513	201 238	1.17	1.2	15	80	< 0.5	< 2	2.25	< 0.5	25	30	90	6.08	10	< 1	0.06	20	1.79	3510	< 1
23514	201 238	1.24	0.4	< 5	130	0.5	< 2	1.33	< 0.5	26	36	73	>15.00	20	< 1	0.03	20	0.85	>10000	< 1
23515	201 238	2.42	0.4	55	190	< 0.5	< 2	0.21	0.5	15	44	81	7.70	10	< 1	0.08	20	1.07	3280	< 1
23516	201 238	1.44	< 0.2	25	160	< 0.5	< 2	0.54	< 0.5	17	23	81	7.28	10	< 1	0.07	30	1.00	6180	1
23517	201 238	1.36	< 0.2	10	70	< 0.5	< 2	3.46	< 0.5	24	22	83	5.87	10	< 1	0.08	20	2.70	3670	< 1
23518	201 238	1.48	< 0.2	15	90	< 0.5	< 2	1.26	< 0.5	26	19	98	7.39	10	< 1	0.09	30	1.34	4990	< 1
23519	201 238	1.53	< 0.2	30	90	< 0.5	< 2	0.79	< 0.5	30	23	112	7.70	10	< 1	0.09	20	1.06	5040	< 1
23520	201 238	1.73	0.4	55	110	< 0.5	< 2	0.90	< 0.5	22	45	89	7.17	20	< 1	0.08	30	1.91	5200	< 1
23521	201 238	0.83	3.0	< 5	50	0.5	< 2	5.14	1.5	17	23	52	3.73	< 10	< 1	0.08	< 10	3.73	1830	< 1
23522	201 238	0.80	2.8	5	60	0.5	< 2	5.67	2.5	17	23	54	3.73	< 10	< 1	0.08	< 10	4.02	2020	< 1
23523	201 238	1.26	0.4	30	80	0.5	< 2	4.79	< 0.5	15	38	63	3.53	< 10	< 1	0.12	10	3.38	1405	< 1
23524	201 238	0.69	1.2	< 5	100	< 0.5	< 2	1.50	< 0.5	13	12	30	4.89	10	< 1	0.08	30	0.71	3200	< 1
23525	201 238	0.85	0.4	< 5	120	< 0.5	< 2	2.01	< 0.5	8	16	16	4.07	10	< 1	0.05	20	1.05	3220	< 1
23526	201 238	0.81	0.8	< 5	70	0.5	< 2	1.31	< 0.5	9	17	19	3.91	10	< 1	0.04	20	0.67	1725	< 1
23527	201 238	0.42	0.8	20	50	0.5	< 2	5.90	1.0	10	11	20	3.11	< 10	< 1	0.03	< 10	3.75	2200	< 1
23528	201 238	0.60	1.4	30	50	< 0.5	< 2	3.76	< 0.5	19	18	41	3.39	< 10	< 1	0.04	10	2.57	1455	< 1
23529	201 238	0.48	1.4	35	40	< 0.5	< 2	5.22	< 0.5	14	20	29	3.03	< 10	1	0.04	< 10	3.49	1335	< 1
23530	201 238	0.61	2.4	20	40	< 0.5	< 2	5.05	1.0	9	11	26	3.26	< 10	< 1	0.05	< 10	3.46	1525	< 1
23531	201 238	0.60	2.0	15	40	< 0.5	< 2	6.75	1.5	6	10	28	3.06	< 10	< 1	0.05	< 10	4.62	1115	< 1
23532	201 238	0.38	1.6	10	30	< 0.5	< 2	9.62	1.5	2	13	19	2.17	< 10	< 1	0.03	< 10	6.57	1200	< 1
23533	201 238	0.79	3.0	< 5	60	< 0.5	< 2	7.11	6.0	8	20	31	3.14	< 10	< 1	0.05	< 10	4.94	2120	< 1
23534	201 238	0.52	1.6	< 5	60	< 0.5	< 2	8.10	< 0.5	5	14	18	3.20	< 10	< 1	0.05	< 10	5.36	2550	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23495	201	238	0.01	19	260	748	15	7	51	0.01	20	< 10	12	< 10	492
23496	201	238	0.01	19	380	604	15	4	37	0.01	10	< 10	13	< 10	626
23497	201	238	0.01	18	450	288	10	4	37	0.01	10	< 10	13	< 10	470
23498	201	238	0.01	43	910	256	10	7	15	0.02	30	< 10	22	< 10	1255
23499	201	238	0.01	29	920	524	10	6	15	0.02	30	< 10	22	< 10	1085
23500	201	238	0.01	36	910	390	10	11	11	0.03	20	< 10	49	< 10	772
23501	201	238	0.01	33	860	510	10	9	15	0.02	20	< 10	44	< 10	1640
23502	201	238	0.01	27	980	568	10	8	12	0.02	10	< 10	40	< 10	806
23503	201	238	0.01	40	730	618	10	8	16	0.02	20	< 10	44	< 10	776
23504	201	238	0.01	32	1360	328	10	11	30	0.01	20	< 10	41	10	1025
23505	201	238	0.01	29	1010	174	10	7	21	0.02	10	< 10	29	< 10	538
23506	201	238	0.01	33	930	238	5	7	14	0.03	20	< 10	37	< 10	2780
23507	201	238	0.01	27	1110	120	10	7	16	0.03	< 10	< 10	33	< 10	1225
23508	201	238	0.01	31	960	214	5	7	20	0.03	< 10	< 10	32	< 10	748
23509	201	238	0.01	57	800	82	5	11	16	0.08	< 10	< 10	100	< 10	408
23510	201	238	0.01	50	1100	40	10	10	15	0.07	< 10	< 10	75	< 10	294
23511	201	238	0.01	48	1190	28	10	11	18	0.06	< 10	< 10	67	< 10	280
23512	201	238	0.01	51	1190	56	10	9	22	0.03	< 10	< 10	42	< 10	334
23513	201	238	0.01	38	950	336	10	9	23	0.03	< 10	< 10	41	< 10	818
23514	201	238	0.01	52	1720	76	10	14	24	0.02	< 10	< 10	47	50	248
23515	201	238	0.01	42	910	54	10	7	12	0.06	< 10	< 10	71	< 10	238
23516	201	238	0.01	53	1070	38	5	10	11	0.05	10	< 10	58	< 10	306
23517	201	238	0.01	40	800	8	5	11	28	0.03	10	< 10	67	< 10	122
23518	201	238	0.01	39	760	16	5	13	17	0.02	10	< 10	64	< 10	150
23519	201	238	0.01	51	750	18	5	14	14	0.02	10	< 10	71	< 10	216
23520	201	238	0.01	46	580	124	15	12	11	0.06	< 10	< 10	58	< 10	626
23521	201	238	0.01	26	760	1210	5	6	27	0.04	10	< 10	32	< 10	2140
23522	201	238	0.02	27	760	1195	5	6	29	0.04	< 10	< 10	32	< 10	2050
23523	201	238	0.02	32	900	62	10	6	38	0.07	< 10	< 10	46	< 10	304
23524	201	238	0.01	25	1340	174	5	5	24	0.01	< 10	< 10	28	< 10	974
23525	201	238	0.01	15	1040	288	< 5	4	25	0.02	< 10	< 10	29	< 10	840
23526	201	238	0.01	19	930	574	5	4	19	0.02	< 10	< 10	28	< 10	1060
23527	201	238	0.01	18	800	730	5	4	57	0.01	< 10	< 10	20	< 10	1210
23528	201	238	0.01	36	810	1065	10	5	36	0.02	< 10	< 10	25	< 10	2050
23529	201	238	0.01	33	790	910	10	4	39	0.01	< 10	< 10	19	< 10	1870
23530	201	238	0.01	18	560	1815	10	5	27	0.02	< 10	< 10	24	< 10	2000
23531	201	238	0.01	17	470	1450	5	4	29	0.02	< 10	< 10	25	< 10	1930
23532	201	238	0.02	14	210	954	< 5	3	23	0.02	< 10	< 10	20	< 10	1750
23533	201	238	0.01	18	440	1875	5	4	22	0.03	< 10	< 10	29	10	4900
23534	201	238	0.02	14	400	480	5	4	23	0.02	< 10	< 10	20	< 10	1315

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23535	201 238	0.73	1.8	15	80	< 0.5	< 2	5.78	2.5	9	17	33	3.51	< 10	< 1	0.06	< 10	4.10	2110	< 1
23536	201 238	0.44	1.0	< 5	50	< 0.5	< 2	9.59	1.0	4	15	28	2.92	< 10	2	0.05	< 10	6.53	1380	< 1
23537	201 238	1.00	0.4	15	110	< 0.5	< 2	0.59	< 0.5	22	12	16	6.23	20	< 1	0.28	50	0.68	2780	< 1
23538	201 238	0.31	0.8	155	50	< 0.5	< 2	12.25	3.5	19	9	16	6.27	< 10	< 1	0.03	< 10	8.30	2420	< 1
23539	201 238	0.30	< 0.2	25	60	< 0.5	< 2	13.95	0.5	1	13	8	3.89	< 10	< 1	0.03	< 10	9.23	3520	< 1
23540	201 238	0.42	< 0.2	5	100	< 0.5	< 2	12.60	< 0.5	< 1	11	6	3.71	< 10	< 1	0.03	< 10	8.47	4150	< 1
23550	201 238	0.44	0.4	30	50	< 0.5	< 2	6.39	1.0	9	14	16	3.28	< 10	< 1	0.05	< 10	4.26	2020	< 1
23551	201 238	0.45	0.6	15	50	< 0.5	< 2	6.76	1.5	9	13	20	3.15	< 10	< 1	0.05	< 10	4.47	1955	< 1
23552	201 238	0.63	0.6	5	60	< 0.5	< 2	6.33	2.0	10	16	30	2.60	< 10	< 1	0.05	< 10	4.29	1335	< 1
23553	201 238	0.63	1.0	20	60	< 0.5	< 2	4.09	4.0	14	16	45	4.01	10	1	0.08	10	2.60	2420	< 1
23554	201 238	0.51	0.4	< 5	70	< 0.5	< 2	5.94	2.0	6	10	17	3.09	< 10	2	0.05	< 10	3.90	2530	< 1
23555	201 238	0.73	1.2	< 5	130	< 0.5	< 2	5.09	< 0.5	10	9	30	5.88	10	2	0.04	10	3.00	6260	< 1
23557	201 238	1.34	< 0.2	20	160	< 0.5	2	1.54	< 0.5	13	25	31	4.75	20	< 1	0.07	30	1.34	3250	< 1
23558	201 238	1.06	0.6	20	80	< 0.5	4	1.87	1.0	13	23	40	4.40	20	1	0.07	20	1.32	2310	< 1
23559	201 238	0.94	1.0	5	70	< 0.5	< 2	4.47	0.5	14	21	34	4.08	10	1	0.08	10	3.14	2580	< 1
23560	201 238	1.14	2.0	40	90	< 0.5	< 2	5.23	1.0	40	33	72	5.68	20	< 1	0.10	< 10	3.13	2850	< 1
23561	201 238	2.02	0.8	25	70	< 0.5	< 2	2.79	0.5	26	43	113	4.85	20	< 1	0.11	20	3.70	2550	< 1
23562	201 238	2.22	< 0.2	< 5	160	< 0.5	6	0.42	< 0.5	19	44	54	5.35	20	< 1	0.09	30	1.30	3070	< 1
23563	201 238	1.60	< 0.2	20	160	< 0.5	< 2	0.56	< 0.5	23	21	48	7.27	20	1	0.23	30	0.89	4620	< 1
23564	201 238	1.27	< 0.2	10	150	< 0.5	< 2	2.30	< 0.5	21	13	41	6.80	20	1	0.16	30	1.84	5130	< 1
23565	201 238	1.67	< 0.2	30	130	< 0.5	< 2	0.75	< 0.5	16	23	41	6.30	10	< 1	0.14	30	0.72	3400	< 1
23676	201 238	3.06	< 0.2	< 5	60	< 0.5	< 2	1.65	< 0.5	10	33	42	4.14	10	< 1	0.08	20	5.10	1450	< 1
23677	201 238	1.05	0.2	30	90	< 0.5	< 2	0.89	< 0.5	15	9	72	6.47	10	< 1	0.09	30	0.56	3490	< 1
23678	201 238	0.74	< 0.2	< 5	100	< 0.5	< 2	1.25	< 0.5	11	7	39	5.94	10	< 1	0.09	30	0.73	4930	< 1
23679	201 238	1.08	0.2	5	150	< 0.5	< 2	0.99	< 0.5	14	9	33	6.22	10	< 1	0.09	30	0.42	4890	1
23680	201 238	0.63	0.2	20	110	< 0.5	< 2	1.96	< 0.5	18	11	50	4.89	10	< 1	0.07	30	1.24	3820	< 1
23681	201 238	0.99	< 0.2	15	40	< 0.5	< 2	1.04	< 0.5	8	5	42	5.36	10	< 1	0.09	20	0.80	1675	< 1
23682	201 238	0.43	0.8	20	70	< 0.5	< 2	3.71	1.5	9	3	51	5.47	< 10	< 1	0.05	20	2.44	4140	< 1
23683	201 238	0.19	0.4	< 5	30	< 0.5	< 2	12.50	3.0	< 1	1	17	2.62	< 10	< 1	0.02	< 10	8.49	2530	< 1
23684	201 238	0.40	1.0	< 5	70	< 0.5	< 2	8.38	4.5	8	5	37	4.02	< 10	< 1	0.04	< 10	5.63	4320	< 1
23685	201 238	0.30	1.0	5	50	< 0.5	< 2	8.88	2.0	14	7	39	3.09	< 10	< 1	0.05	< 10	5.94	2580	< 1
23686	201 238	0.89	1.0	35	90	< 0.5	2	0.69	3.5	27	16	41	3.92	10	< 1	0.08	30	0.54	1740	< 1
23687	201 238	0.66	1.2	20	60	< 0.5	< 2	2.41	1.5	32	11	74	4.65	< 10	< 1	0.13	30	1.58	1375	< 1
23688	201 238	0.65	2.4	20	40	< 0.5	< 2	3.27	3.0	19	12	39	3.08	< 10	< 1	0.14	20	2.52	925	< 1
23697	201 238	1.40	2.8	15	130	< 0.5	< 2	1.54	1.5	13	23	28	4.33	< 10	1	0.08	20	1.16	1515	< 1
23698	201 238	1.45	1.0	10	240	< 0.5	< 2	1.79	1.5	13	28	35	4.24	10	< 1	0.07	20	1.28	1530	< 1
23699	201 238	1.05	4.2	15	80	< 0.5	< 2	3.34	3.0	14	17	36	4.28	< 10	< 1	0.10	20	2.34	2180	< 1
23700	201 238	1.62	< 0.2	15	190	< 0.5	< 2	0.33	< 0.5	8	28	26	4.45	10	< 1	0.05	20	0.50	790	< 1
23701	201 238	1.93	0.2	5	180	< 0.5	< 2	0.20	< 0.5	9	28	15	3.76	10	< 1	0.06	20	0.50	885	< 1
23705	201 238	1.73	4.2	35	50	0.5	< 2	1.27	7.5	38	38	118	7.09	10	< 1	0.17	20	1.51	1870	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23535	201 238	0.01	17	450	588	5	4	15	0.03	10	< 10	28	< 10	1250
23536	201 238	0.02	10	320	292	5	4	22	0.02	20	< 10	17	< 10	924
23537	201 238	0.01	26	710	138	5	11	9	0.02	< 10	< 10	19	< 10	354
23538	201 238	0.02	27	130	104	15	4	20	0.01	10	< 10	14	< 10	262
23539	201 238	0.02	14	140	50	10	3	28	0.01	10	< 10	14	< 10	148
23540	201 238	0.02	8	290	30	5	3	20	0.01	< 10	< 10	15	< 10	128
23550	201 238	0.01	15	510	88	5	5	39	0.02	< 10	< 10	19	< 10	416
23551	201 238	0.01	17	560	422	5	4	39	0.01	< 10	< 10	18	< 10	942
23552	201 238	0.02	20	650	238	5	4	38	0.03	< 10	< 10	27	< 10	830
23553	201 238	0.01	21	880	558	5	5	31	0.01	10	< 10	23	< 10	2110
23554	201 238	0.01	12	700	316	5	4	28	0.01	< 10	< 10	20	< 10	824
23555	201 238	0.01	14	1090	96	10	4	36	0.01	< 10	< 10	22	< 10	226
23557	201 238	0.01	28	880	74	5	6	17	0.03	< 10	< 10	47	< 10	198
23558	201 238	0.01	26	1220	82	5	5	14	0.02	< 10	< 10	41	< 10	330
23559	201 238	0.01	29	1010	72	10	6	21	0.03	< 10	< 10	38	< 10	406
23560	201 238	0.01	54	920	452	10	7	32	0.05	< 10	< 10	44	10	1140
23561	201 238	0.01	48	770	126	5	9	18	0.07	< 10	< 10	59	< 10	694
23562	201 238	0.01	38	530	82	5	8	12	0.08	< 10	< 10	64	< 10	262
23563	201 238	0.01	37	920	10	< 5	9	13	0.05	< 10	< 10	43	< 10	106
23564	201 238	0.01	32	920	12	5	9	23	0.04	< 10	< 10	38	< 10	86
23565	201 238	0.01	28	990	26	5	7	14	0.04	< 10	< 10	39	< 10	130
23676	201 238	0.01	19	780	44	5	9	13	0.07	< 10	< 10	61	< 10	488
23677	201 238	0.01	21	1200	32	5	6	14	0.02	< 10	< 10	28	< 10	186
23678	201 238	0.01	22	990	48	5	5	16	0.01	10	< 10	17	< 10	160
23679	201 238	0.01	20	1680	62	10	5	25	0.01	20	< 10	25	< 10	152
23680	201 238	0.01	24	910	44	5	5	25	0.03	10	< 10	26	< 10	108
23681	201 238	0.01	16	1170	30	5	5	14	0.01	< 10	< 10	21	< 10	114
23682	201 238	0.01	12	740	150	5	6	19	0.01	10	< 10	13	< 10	1400
23683	201 238	0.02	4	240	140	10	3	21	< 0.01	< 10	< 10	7	< 10	1550
23684	201 238	0.02	15	450	304	5	4	26	0.01	10	< 10	15	< 10	2490
23685	201 238	0.01	17	470	202	10	4	25	0.01	10	< 10	13	< 10	1200
23686	201 238	0.01	34	780	516	5	6	16	0.05	10	< 10	37	< 10	3240
23687	201 238	0.01	38	740	654	10	10	23	0.02	10	< 10	31	< 10	1045
23688	201 238	0.01	23	610	1200	10	5	14	0.03	10	< 10	21	< 10	1690
23697	201 238	0.01	25	1110	1120	5	6	22	0.04	< 10	< 10	45	< 10	886
23698	201 238	0.01	21	1120	538	5	6	23	0.03	10	< 10	49	< 10	684
23699	201 238	0.01	23	730	1850	10	6	20	0.04	< 10	< 10	32	< 10	2090
23700	201 238	0.01	23	490	22	5	8	15	0.05	< 10	< 10	45	< 10	78
23701	201 238	0.01	22	830	44	5	2	14	0.04	< 10	< 10	57	< 10	174
23705	201 238	0.01	112	670	2110	10	17	7	0.01	< 10	< 10	104	< 10	3250

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23706	201	238	0.37	7.0	25	20	0.5	< 2	10.45	12.0	10	5	31	2.31	< 10	< 1	0.04	< 10	6.43	710	< 1
23707	201	238	0.41	13.4	60	30	0.5	< 2	6.95	15.0	17	5	56	3.29	< 10	< 1	0.04	< 10	4.12	1365	< 1
23708	201	238	0.29	33.6	65	20	< 0.5	2	9.19	8.5	21	5	56	3.06	< 10	< 1	0.03	< 10	5.46	1090	< 1
23709	201	238	0.37	13.4	30	30	0.5	2	7.87	3.0	21	5	39	2.80	< 10	< 1	0.08	< 10	4.67	1275	< 1
23710	201	238	0.53	7.8	40	30	0.5	< 2	6.66	3.5	17	9	44	3.07	< 10	< 1	0.08	< 10	4.02	970	< 1
23711	201	238	0.47	2.4	15	40	0.5	< 2	8.52	6.5	16	8	28	2.35	< 10	< 1	0.05	< 10	5.15	1485	< 1
23712	201	238	0.48	2.8	30	50	< 0.5	< 2	5.91	6.5	17	7	33	3.36	< 10	< 1	0.05	< 10	3.42	2310	< 1
23713	201	238	0.77	1.6	30	80	< 0.5	< 2	0.84	1.0	17	12	42	5.28	< 10	< 1	0.07	20	0.46	2370	1
23714	201	238	1.08	1.2	35	70	< 0.5	< 2	1.33	< 0.5	21	17	50	5.07	< 10	< 1	0.09	20	0.97	2810	1
23715	201	238	0.48	0.6	10	80	< 0.5	< 2	3.27	< 0.5	16	7	29	5.51	< 10	< 1	0.05	10	1.83	3960	< 1
23716	201	238	0.72	0.8	25	90	< 0.5	< 2	1.46	< 0.5	17	12	40	4.96	< 10	< 1	0.06	20	0.75	2640	< 1
23717	201	238	1.18	0.6	25	110	< 0.5	< 2	0.95	< 0.5	16	16	22	4.06	< 10	< 1	0.06	20	0.42	1955	< 1
23718	201	238	0.63	0.4	30	100	< 0.5	< 2	0.56	< 0.5	16	14	41	6.92	< 10	< 1	0.03	20	0.36	3520	< 1
23719	201	238	0.91	0.6	15	90	< 0.5	< 2	1.14	< 0.5	15	14	22	3.71	< 10	< 1	0.06	20	0.53	1935	< 1
23720	201	238	1.79	0.6	25	130	< 0.5	2	0.60	< 0.5	21	25	23	4.90	< 10	< 1	0.07	20	1.39	2090	< 1
23721	201	238	2.14	0.6	25	170	< 0.5	< 2	0.41	< 0.5	19	32	29	4.75	10	1	0.08	20	1.16	1240	< 1
23722	201	238	1.30	0.8	20	120	< 0.5	< 2	0.65	< 0.5	15	21	37	5.50	< 10	< 1	0.10	30	0.68	2280	1
23733	201	238	1.42	1.6	50	140	< 0.5	< 2	0.88	2.5	21	22	44	5.11	< 10	< 1	0.13	30	0.91	2150	1
23734	201	238	2.58	0.8	20	80	< 0.5	2	0.67	< 0.5	17	28	28	3.33	< 10	< 1	0.31	30	2.54	560	< 1
23735	201	238	1.12	1.8	55	110	< 0.5	< 2	1.77	2.5	17	16	26	5.08	< 10	1	0.08	20	1.01	2160	< 1
23736	201	238	0.94	0.8	25	90	< 0.5	< 2	1.17	< 0.5	16	13	36	3.35	< 10	< 1	0.17	20	0.75	1160	< 1
23737	201	238	1.32	1.2	55	90	< 0.5	< 2	1.39	1.5	22	21	63	4.59	< 10	< 1	0.11	20	1.00	2290	< 1
23738	201	238	0.80	0.6	30	60	< 0.5	< 2	0.52	< 0.5	14	12	46	4.41	< 10	< 1	0.06	20	0.31	1930	< 1
23739	201	238	0.47	0.6	25	80	< 0.5	< 2	1.51	< 0.5	17	9	42	4.80	< 10	< 1	0.05	20	0.80	2970	< 1
23740	201	238	1.27	0.4	25	120	< 0.5	< 2	0.88	< 0.5	16	18	38	5.08	< 10	< 1	0.17	20	1.41	3430	< 1
23741	201	238	2.14	0.2	20	90	< 0.5	< 2	0.81	< 0.5	28	29	68	6.82	< 10	< 1	0.08	20	1.81	1780	< 1
23742	201	238	0.61	0.4	40	90	< 0.5	< 2	1.63	< 0.5	15	8	24	7.55	< 10	< 1	0.04	20	0.75	5430	< 1
23743	201	238	0.98	0.4	25	80	< 0.5	< 2	1.27	< 0.5	13	13	31	6.94	< 10	1	0.07	20	0.80	3950	< 1
23744	201	238	0.78	0.8	35	100	< 0.5	< 2	2.32	< 0.5	19	14	43	5.30	< 10	< 1	0.06	20	1.10	4020	< 1
23745	201	238	0.77	0.8	35	140	< 0.5	< 2	1.01	1.5	20	12	52	7.14	< 10	1	0.10	30	0.66	5140	< 1
23746	201	238	0.77	0.8	50	140	< 0.5	< 2	0.72	< 0.5	25	14	60	6.71	< 10	1	0.08	30	0.48	5020	1
23747	201	238	1.45	0.6	40	110	< 0.5	< 2	0.87	< 0.5	19	18	65	6.07	< 10	< 1	0.10	20	1.35	4490	< 1
23748	201	238	0.46	0.8	20	70	< 0.5	< 2	5.09	1.0	15	8	42	3.72	< 10	< 1	0.06	< 10	3.04	2410	< 1
23749	201	238	0.25	0.6	25	60	< 0.5	< 2	5.73	2.0	13	4	22	4.32	< 10	< 1	0.04	< 10	3.37	4080	< 1
23750	201	238	0.50	1.2	40	60	< 0.5	< 2	5.47	3.0	24	8	46	3.75	< 10	< 1	0.05	< 10	3.28	2870	< 1
23751	201	238	0.64	1.8	55	70	< 0.5	< 2	4.82	2.5	34	11	42	3.14	< 10	< 1	0.08	< 10	2.91	1690	< 1
23752	201	238	0.66	1.6	30	50	< 0.5	< 2	1.20	1.0	27	10	29	4.91	< 10	< 1	0.11	40	0.49	1480	< 1
23753	201	238	0.51	44.0	50	30	< 0.5	< 2	6.01	8.0	26	7	52	3.50	< 10	< 1	0.12	< 10	3.73	1170	< 1
23754	201	238	1.24	1.4	10	70	0.5	< 2	3.31	1.0	28	13	47	3.77	< 10	< 1	0.29	30	2.19	935	1
23755	201	238	0.31	13.4	50	20	0.5	< 2	7.23	6.5	22	6	57	3.24	< 10	< 1	0.05	< 10	4.49	1140	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Pa o. .7-B
Tot. Pages: 9
Date :16-JUL-89
Invoice # :I-8919848
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23706	201	238	0.01	14	400	3050	10	3	16	0.01	< 10	< 10	13	< 10	6150
23707	201	238	0.01	24	580	6090	20	4	13	0.01	< 10	< 10	16	< 10	7490
23708	201	238	0.01	24	520	>10000	35	3	26	0.01	< 10	< 10	14	< 10	6760
23709	201	238	0.01	22	720	7160	15	4	21	0.01	< 10	< 10	16	< 10	3000
23710	201	238	0.01	23	670	2870	10	5	13	0.01	< 10	< 10	20	< 10	4020
23711	201	238	0.01	14	440	790	5	3	13	0.02	< 10	< 10	18	< 10	5000
23712	201	238	0.01	17	690	1580	5	5	13	0.02	< 10	< 10	20	< 10	3520
23713	201	238	0.01	20	910	392	< 5	7	13	0.02	< 10	< 10	25	< 10	1295
23714	201	238	0.01	27	990	108	< 5	6	24	0.02	< 10	< 10	32	< 10	476
23715	201	238	0.01	22	720	34	< 5	6	24	0.01	< 10	< 10	21	< 10	194
23716	201	238	0.01	25	970	44	< 5	6	22	0.02	< 10	< 10	23	< 10	130
23717	201	238	0.01	19	1690	40	< 5	4	25	0.02	< 10	< 10	27	< 10	96
23718	201	238	< 0.01	21	870	16	< 5	7	9	0.01	< 10	< 10	27	< 10	98
23719	201	238	0.01	15	1390	24	< 5	3	15	0.02	< 10	< 10	25	< 10	118
23720	201	238	0.01	23	840	24	< 5	8	12	0.08	< 10	< 10	61	< 10	220
23721	201	238	0.01	27	950	30	< 5	8	12	0.11	< 10	< 10	86	< 10	228
23722	201	238	0.01	26	1320	26	< 5	8	15	0.05	< 10	< 10	51	< 10	264
23733	201	238	0.01	34	700	450	5	7	12	0.03	< 10	< 10	39	< 10	2160
23734	201	238	0.01	27	740	92	< 5	7	10	0.03	< 10	< 10	34	< 10	274
23735	201	238	0.01	26	810	556	5	6	14	0.02	< 10	< 10	33	< 10	2110
23736	201	238	0.01	20	840	234	5	3	11	0.02	< 10	< 10	18	< 10	388
23737	201	238	0.01	25	1010	428	< 5	5	14	0.03	< 10	< 10	33	< 10	1435
23738	201	238	< 0.01	17	1000	26	5	5	10	0.02	< 10	< 10	22	< 10	122
23739	201	238	< 0.01	19	750	28	5	5	15	0.01	< 10	< 10	16	< 10	164
23740	201	238	0.01	25	860	28	< 5	7	11	0.02	< 10	< 10	26	< 10	360
23741	201	238	0.01	29	770	30	5	14	11	0.09	< 10	< 10	101	< 10	368
23742	201	238	< 0.01	20	1240	62	5	5	15	0.01	< 10	< 10	21	< 10	192
23743	201	238	0.01	23	1430	44	5	6	19	0.01	< 10	< 10	20	< 10	144
23744	201	238	0.01	25	1310	50	5	6	28	0.02	< 10	< 10	25	< 10	144
23745	201	238	0.01	26	1150	112	5	7	22	0.02	< 10	< 10	22	< 10	634
23746	201	238	0.01	34	1060	60	5	7	23	0.02	< 10	< 10	28	< 10	120
23747	201	238	0.01	26	1360	62	5	8	20	0.02	< 10	< 10	30	< 10	168
23748	201	238	0.01	14	730	142	5	5	20	0.02	< 10	< 10	17	< 10	948
23749	201	238	0.01	12	520	108	5	5	22	< 0.01	< 10	< 10	10	< 10	1150
23750	201	238	0.01	23	830	300	10	5	16	0.02	< 10	< 10	19	< 10	2940
23751	201	238	0.01	29	780	890	5	5	17	0.03	< 10	< 10	26	< 10	3120
23752	201	238	0.01	26	1630	516	5	7	20	0.01	< 10	< 10	21	< 10	1130
23753	201	238	0.01	26	740	>10000	40	5	21	0.02	< 10	< 10	23	< 10	5820
23754	201	238	0.01	22	1730	454	5	6	34	0.02	< 10	< 10	26	< 10	878
23755	201	238	0.01	31	420	6860	30	4	20	0.01	< 10	< 10	14	< 10	5610

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23756	201 238	0.28	43.0	85	20	0.5	< 2	10.05	15.0	21	4	76	3.77	< 10	< 1	0.02	< 10	6.18	1450	< 1
23757	201 238	0.14	31.0	60	10	< 0.5	< 2	11.65	28.0	15	1	110	2.81	< 10	< 1	0.01	< 10	7.14	1615	< 1
23758	201 238	0.18	116.0	240	10	< 0.5	< 2	8.93	31.0	26	2	189	6.90	< 10	3	0.02	< 10	5.32	1500	1
23759	201 238	0.23	26.8	85	20	< 0.5	< 2	10.50	13.0	20	3	100	5.75	< 10	2	0.02	< 10	6.57	1715	< 1
23760	201 238	0.31	16.0	45	10	< 0.5	< 2	10.80	18.5	13	4	58	2.75	< 10	< 1	0.02	< 10	6.75	1005	< 1
23761	201 238	0.28	16.8	75	20	< 0.5	< 2	9.93	9.5	15	4	51	3.11	< 10	< 1	0.03	< 10	6.15	1165	< 1
23762	201 238	0.28	34.6	90	20	< 0.5	< 2	9.74	11.5	17	5	88	3.57	< 10	< 1	0.03	< 10	6.06	1310	< 1
23763	201 238	0.37	41.4	85	30	< 0.5	< 2	8.44	13.5	20	7	69	3.77	< 10	< 1	0.04	< 10	5.27	1315	< 1
23764	201 238	0.59	3.0	20	50	< 0.5	< 2	1.37	4.5	6	11	23	2.97	< 10	< 1	0.05	20	0.56	1495	< 1
23765	201 238	0.53	2.8	35	40	< 0.5	< 2	3.59	1.5	18	9	37	3.01	< 10	< 1	0.10	10	2.29	1020	1
23766	201 238	0.31	1.0	25	30	< 0.5	< 2	9.57	2.0	14	6	32	2.15	< 10	< 1	0.04	< 10	5.96	1225	< 1
23767	201 238	0.52	2.4	35	40	< 0.5	< 2	5.06	5.5	22	10	37	2.82	< 10	< 1	0.04	< 10	3.17	1750	< 1
23768	201 238	0.36	1.2	20	50	< 0.5	< 2	5.65	1.5	17	7	38	3.44	< 10	< 1	0.03	< 10	3.42	2700	1
23769	201 238	0.43	1.0	30	50	< 0.5	< 2	3.91	1.0	14	7	33	4.19	< 10	< 1	0.05	< 10	2.30	2620	< 1
23770	201 238	0.29	0.8	25	60	< 0.5	< 2	5.39	1.5	17	7	30	3.59	< 10	< 1	0.03	< 10	3.20	2910	< 1
23771	201 238	1.03	0.8	40	100	< 0.5	< 2	1.09	< 0.5	26	21	70	5.92	< 10	< 1	0.07	30	0.83	3090	1
23772	201 238	0.79	0.8	35	110	< 0.5	< 2	1.03	< 0.5	18	14	35	6.17	< 10	< 1	0.06	30	0.44	3350	1
23773	201 238	0.79	0.4	35	110	< 0.5	< 2	1.10	< 0.5	17	13	34	6.47	< 10	< 1	0.05	30	0.56	4250	< 1
23774	201 238	0.66	0.6	35	110	0.5	< 2	0.98	< 0.5	14	11	31	5.94	< 10	< 1	0.05	20	0.46	4320	< 1
23775	201 238	0.92	0.6	35	100	0.5	< 2	0.93	< 0.5	15	15	44	6.14	< 10	1	0.06	20	0.56	3570	< 1
23776	201 238	1.13	0.8	30	110	< 0.5	< 2	0.69	< 0.5	15	17	38	4.68	< 10	< 1	0.11	20	0.77	2670	1
23777	201 238	1.55	0.6	40	230	< 0.5	< 2	0.65	< 0.5	20	25	81	7.35	< 10	< 1	0.08	20	0.69	4820	1
23778	201 238	1.90	0.4	15	110	0.5	< 2	0.60	< 0.5	14	26	36	4.66	< 10	< 1	0.09	20	1.46	940	< 1
23779	201 238	0.58	0.6	20	80	< 0.5	< 2	0.72	< 0.5	12	10	38	5.07	< 10	< 1	0.05	20	0.35	2310	1
23780	203 238	0.83	0.4	5	120	< 0.5	< 2	1.54	< 0.5	11	31	8	2.58	< 10	< 1	0.27	10	0.59	2360	< 1
23781	203 238	0.38	0.2	5	110	< 0.5	< 2	0.85	< 0.5	11	33	7	2.12	< 10	< 1	0.18	10	0.30	1575	< 1
23782	201 238	0.48	0.2	35	90	< 0.5	< 2	0.80	< 0.5	16	6	8	4.16	< 10	< 1	0.06	10	0.25	2510	1
23783	201 238	0.77	1.0	155	70	< 0.5	< 2	5.66	7.5	26	12	64	5.90	< 10	4	0.05	< 10	3.96	1895	1
23784	201 238	1.41	1.0	75	120	< 0.5	< 2	1.05	2.0	24	18	29	5.12	< 10	< 1	0.19	20	1.44	1370	1
23785	201 238	1.08	1.4	95	110	< 0.5	< 2	0.66	2.0	37	15	44	6.69	< 10	< 1	0.14	20	0.82	910	1
23786	201 238	1.00	3.0	145	100	< 0.5	< 2	0.55	9.0	24	15	61	6.54	< 10	1	0.08	20	0.55	1765	2
23787	201 238	1.49	1.0	30	120	< 0.5	< 2	2.33	3.0	22	23	53	4.83	< 10	< 1	0.16	20	2.04	2250	1
23788	201 238	1.05	11.4	180	50	< 0.5	< 2	4.09	26.5	19	17	40	4.92	< 10	10	0.05	< 10	2.82	1265	1
23789	201 238	1.30	1.4	65	120	< 0.5	< 2	0.55	2.5	19	20	55	6.20	< 10	< 1	0.09	20	0.60	2210	2
23790	201 238	1.66	1.8	135	110	< 0.5	< 2	1.23	3.5	37	41	113	7.98	< 10	< 1	0.11	10	1.23	2010	1
23791	201 238	1.10	1.6	105	130	< 0.5	< 2	1.15	1.0	20	17	47	6.33	< 10	< 1	0.07	20	0.88	2100	3
23803	201 238	1.38	0.4	30	150	< 0.5	< 2	1.07	1.5	13	17	10	4.24	< 10	< 1	0.08	20	0.49	2400	< 1
23804	201 238	1.61	1.0	30	190	< 0.5	< 2	0.69	1.5	15	26	14	4.39	< 10	< 1	0.08	20	0.54	2100	< 1
23805	201 238	1.32	0.8	15	120	< 0.5	< 2	0.67	1.0	15	14	21	3.69	< 10	< 1	0.28	20	0.85	2450	< 1
23806	201 238	1.49	1.4	40	130	< 0.5	< 2	0.51	2.0	15	25	72	5.33	< 10	< 1	0.13	30	0.73	1795	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23756	201	238	0.01	26	280	>10000	80	3	19	0.01	< 10	< 10	13	< 10	>10000
23757	201	238	0.01	18	220	>10000	60	2	20	< 0.01	< 10	< 10	7	10	>10000
23758	201	238	0.01	37	230	>10000	380	3	15	< 0.01	< 10	< 10	10	10	>10000
23759	201	238	0.01	20	220	>10000	40	2	13	< 0.01	< 10	< 10	10	< 10	>10000
23760	201	238	0.01	15	300	>10000	20	2	17	0.01	< 10	< 10	12	< 10	>10000
23761	201	238	0.01	23	370	8960	30	3	15	0.01	< 10	< 10	12	< 10	6940
23762	201	238	0.01	22	350	>10000	45	3	19	0.01	< 10	< 10	14	< 10	8770
23763	201	238	0.01	27	370	>10000	55	4	19	0.01	< 10	< 10	16	< 10	9290
23764	201	238	0.01	11	970	1635	5	3	9	0.01	< 10	< 10	19	< 10	1800
23765	201	238	0.01	22	960	1115	10	5	17	0.01	< 10	< 10	19	< 10	2200
23766	201	238	0.01	12	430	414	5	3	17	0.01	< 10	< 10	13	< 10	2240
23767	201	238	0.01	19	620	1405	10	4	14	0.02	< 10	< 10	20	< 10	4680
23768	201	238	0.01	16	560	478	5	5	21	0.01	< 10	< 10	15	< 10	1510
23769	201	238	0.01	16	730	138	5	5	19	0.01	< 10	< 10	15	< 10	1295
23770	201	238	0.01	18	710	170	5	4	24	0.01	< 10	< 10	12	< 10	1185
23771	201	238	0.01	38	1020	118	5	9	21	0.03	< 10	< 10	44	< 10	438
23772	201	238	< 0.01	28	1180	70	5	5	18	0.02	< 10	< 10	24	< 10	234
23773	201	238	0.01	29	1010	36	5	6	26	0.01	< 10	< 10	25	< 10	110
23774	201	238	< 0.01	19	960	60	5	4	16	0.01	< 10	< 10	19	< 10	140
23775	201	238	< 0.01	22	1100	26	< 5	6	13	0.01	< 10	< 10	28	< 10	116
23776	201	238	0.01	23	880	34	< 5	6	12	0.03	< 10	< 10	33	< 10	160
23777	201	238	0.01	26	1330	30	< 5	8	14	0.05	< 10	< 10	74	< 10	188
23778	201	238	0.01	25	1050	18	5	8	12	0.09	< 10	< 10	65	< 10	246
23779	201	238	< 0.01	15	940	36	< 5	6	11	0.01	< 10	< 10	20	< 10	178
23780	203	238	0.01	12	1280	20	< 5	2	13	0.01	< 10	< 10	10	< 10	156
23781	203	238	< 0.01	11	720	12	< 5	2	6	< 0.01	< 10	< 10	5	< 10	116
23782	201	238	< 0.01	18	810	62	< 5	3	8	< 0.01	< 10	< 10	9	< 10	254
23783	201	238	0.01	52	450	224	5	5	12	0.02	< 10	< 10	18	< 10	4230
23784	201	238	0.01	51	610	212	5	6	7	0.02	< 10	< 10	26	< 10	2540
23785	201	238	0.01	45	580	198	5	7	7	0.02	< 10	< 10	23	< 10	3180
23786	201	238	< 0.01	57	590	270	5	6	6	0.02	< 10	< 10	25	< 10	8800
23787	201	238	0.01	39	530	144	5	6	14	0.03	< 10	< 10	35	< 10	2080
23788	201	238	0.01	45	700	8350	10	4	12	0.03	< 10	< 10	29	< 10	>10000
23789	201	238	0.01	36	590	192	5	7	8	0.02	< 10	< 10	37	< 10	2980
23790	201	238	0.01	53	570	504	5	14	12	0.06	< 10	< 10	89	< 10	2630
23791	201	238	0.01	48	670	116	5	7	11	0.03	< 10	< 10	30	< 10	1810
23803	201	238	0.01	15	920	164	< 5	3	12	0.04	< 10	< 10	38	< 10	1000
23804	201	238	0.01	23	780	648	< 5	6	14	0.05	< 10	< 10	43	< 10	1555
23805	201	238	0.01	22	860	420	< 5	4	8	0.03	< 10	< 10	21	< 10	834
23806	201	238	0.01	27	680	402	< 5	7	11	0.04	< 10	< 10	37	< 10	2200

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date :16-JUL-89
Invoice # :I-8919848
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23807	201	238	0.93	1.2	25	100	< 0.5	< 2	1.43	2.5	14	15	28	4.80	< 10	2	0.09	20	0.83	2400	< 1
23808	201	238	1.26	1.2	40	130	< 0.5	< 2	2.05	0.5	16	19	56	4.46	< 10	2	0.12	20	1.61	1705	1
23809	201	238	1.16	1.4	35	140	< 0.5	< 2	1.15	3.0	15	15	32	4.47	< 10	< 1	0.09	20	0.52	2920	1
23810	201	238	1.20	0.6	5	130	< 0.5	< 2	1.92	1.5	11	17	35	2.94	< 10	< 1	0.10	10	0.71	1220	< 1
23811	201	238	1.57	0.4	30	110	< 0.5	< 2	0.59	< 0.5	16	21	50	3.97	< 10	< 1	0.18	30	1.12	1450	1
23812	201	238	0.57	0.4	15	40	< 0.5	< 2	3.81	< 0.5	14	8	30	2.78	< 10	< 1	0.11	< 10	2.31	1165	1
23813	203	238	1.28	0.6	10	70	< 0.5	< 2	2.43	< 0.5	11	32	31	2.21	< 10	< 1	0.35	10	1.74	890	1
23814	201	238	1.54	0.8	15	90	< 0.5	< 2	1.83	< 0.5	14	20	35	3.64	< 10	< 1	0.24	20	1.76	1480	1
23815	201	238	1.23	0.6	25	110	< 0.5	< 2	2.31	0.5	14	19	48	4.16	< 10	1	0.20	20	1.85	1470	1
23816	201	238	1.56	0.4	20	180	< 0.5	< 2	0.77	0.5	12	24	28	4.80	< 10	< 1	0.11	30	0.70	1845	1
23817	201	238	1.19	0.4	20	130	< 0.5	< 2	1.99	0.5	11	18	37	3.08	< 10	< 1	0.11	10	0.76	1350	1
23818	201	238	1.85	0.4	20	140	< 0.5	< 2	1.08	< 0.5	13	25	22	3.63	< 10	< 1	0.18	20	1.15	1040	1
24461	201	238	1.10	1.2	30	110	< 0.5	< 2	0.91	2.0	16	16	28	5.92	< 10	4	0.06	30	0.64	3230	1
24462	201	238	1.34	1.0	15	110	< 0.5	< 2	0.84	2.5	13	20	21	5.74	< 10	< 1	0.05	30	0.51	3270	1
24463	201	238	1.31	1.0	25	150	< 0.5	< 2	0.61	1.0	13	19	21	5.62	< 10	< 1	0.06	20	0.42	3220	1
24464	201	238	1.15	0.8	40	200	< 0.5	< 2	1.08	< 0.5	12	17	37	5.66	< 10	< 1	0.07	30	0.54	3020	3
24465	201	238	1.00	0.6	40	90	< 0.5	< 2	2.91	0.5	25	13	26	6.60	< 10	< 1	0.08	10	1.24	3250	1
24466	201	238	0.72	0.8	35	100	< 0.5	< 2	4.90	< 0.5	21	9	30	4.60	< 10	< 1	0.08	< 10	2.74	2350	2
24467	201	238	0.55	0.6	20	70	< 0.5	< 2	1.83	0.5	14	8	21	3.61	< 10	< 1	0.06	30	1.04	1995	1
24468	201	238	0.95	1.2	25	120	< 0.5	< 2	0.73	1.5	19	18	32	6.31	< 10	2	0.05	30	0.41	3830	1
24469	201	238	0.51	1.2	30	70	< 0.5	< 2	5.44	1.5	15	10	24	4.05	< 10	< 1	0.05	< 10	3.10	2270	< 1
24470	201	238	0.74	1.2	35	80	0.5	< 2	1.93	1.0	19	13	28	5.53	< 10	< 1	0.09	30	0.92	2350	< 1
24471	201	238	0.44	0.6	30	70	0.5	< 2	4.50	0.5	16	8	22	3.83	< 10	1	0.08	< 10	2.49	2310	< 1
24472	201	238	0.54	2.2	60	70	0.5	< 2	4.59	3.5	25	9	36	4.92	< 10	< 1	0.06	< 10	2.68	1870	< 1
24473	201	238	0.45	6.8	25	40	0.5	< 2	7.17	8.5	14	8	36	3.26	< 10	< 1	0.05	< 10	4.20	1640	< 1
24474	201	238	0.74	3.2	40	90	0.5	< 2	3.30	6.5	20	12	47	4.79	< 10	< 1	0.06	10	1.86	2730	< 1
24475	201	238	0.49	3.2	60	60	0.5	< 2	4.92	7.0	15	9	37	4.99	< 10	< 1	0.05	< 10	2.52	2680	< 1
24476	201	238	0.37	1.8	35	50	0.5	< 2	9.25	6.5	15	6	38	3.47	< 10	< 1	0.04	< 10	5.39	2090	< 1
24871	201	238	0.38	0.8	65	50	< 0.5	< 2	7.09	0.5	14	6	23	4.90	< 10	< 1	0.03	< 10	4.04	3030	< 1
24872	201	238	0.21	10.6	20	30	< 0.5	< 2	12.45	3.5	15	5	44	3.06	< 10	< 1	0.02	< 10	6.91	2070	1
24873	201	238	0.40	0.4	5	30	< 0.5	2	9.45	< 0.5	7	5	11	1.72	< 10	< 1	0.13	< 10	1.15	1255	< 1
24874	201	238	1.08	1.0	20	120	0.5	< 2	0.40	< 0.5	11	20	24	4.66	< 10	< 1	0.05	30	0.38	1545	1
24875	201	238	0.90	5.2	50	70	0.5	< 2	5.91	4.5	16	16	42	5.77	< 10	< 1	0.04	< 10	3.59	4520	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 16-JUL-89
Invoice # : I-8919848
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8919848

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23807	201 238	0.01	20	780	446	< 5	5	12	0.01	< 10	< 10	24	< 10	1640
23808	201 238	0.01	27	750	346	5	6	13	0.03	< 10	< 10	30	< 10	1170
23809	201 238	0.01	22	1020	574	< 5	4	11	0.02	< 10	< 10	27	< 10	1565
23810	201 238	0.01	16	1010	212	< 5	3	16	0.02	< 10	< 10	27	< 10	762
23811	201 238	0.01	28	610	212	< 5	6	10	0.03	< 10	< 10	33	< 10	484
23812	201 238	0.01	18	510	24	< 5	3	15	0.01	< 10	< 10	15	< 10	128
23813	203 238	0.01	18	900	94	< 5	3	14	0.01	< 10	< 10	19	< 10	216
23814	201 238	0.01	23	670	150	< 5	6	11	0.02	< 10	< 10	29	< 10	482
23815	201 238	0.01	30	590	142	< 5	7	13	0.03	< 10	< 10	33	< 10	552
23816	201 238	0.01	23	470	104	< 5	6	12	0.04	< 10	< 10	45	< 10	452
23817	201 238	0.01	16	840	70	< 5	4	17	0.03	< 10	< 10	28	< 10	492
23818	201 238	0.01	20	630	82	< 5	6	14	0.04	< 10	< 10	41	< 10	440
24461	201 238	0.01	26	590	582	< 5	8	13	0.03	< 10	< 10	35	< 10	1610
24462	201 238	< 0.01	22	940	554	< 5	6	12	0.03	< 10	< 10	37	< 10	1725
24463	201 238	< 0.01	23	760	404	< 5	6	12	0.03	< 10	< 10	37	< 10	1250
24464	201 238	0.01	27	1190	200	5	4	14	0.02	< 10	< 10	34	< 10	642
24465	201 238	< 0.01	29	1090	268	5	5	27	0.01	< 10	< 10	39	< 10	708
24466	201 238	0.01	32	680	238	5	5	32	0.02	< 10	< 10	25	< 10	810
24467	201 238	0.01	21	620	244	5	5	23	0.01	< 10	< 10	18	< 10	542
24468	201 238	< 0.01	27	810	488	5	8	18	0.02	< 10	< 10	35	< 10	1195
24469	201 238	0.01	19	530	378	< 5	5	44	0.01	< 10	< 10	19	< 10	1535
24470	201 238	0.01	23	930	402	5	6	32	0.01	< 10	< 10	25	< 10	1400
24471	201 238	0.01	21	520	128	5	6	41	0.01	< 10	< 10	15	< 10	658
24472	201 238	0.01	27	480	1340	5	6	34	0.01	< 10	< 10	19	< 10	2660
24473	201 238	0.01	19	380	4570	10	5	32	0.01	< 10	< 10	17	< 10	5810
24474	201 238	0.01	25	590	2220	5	6	23	0.02	< 10	< 10	25	< 10	5030
24475	201 238	0.01	25	950	1775	5	5	53	0.01	< 10	< 10	21	< 10	4820
24476	201 238	0.01	18	350	1145	5	4	22	0.01	< 10	< 10	15	< 10	3810
24871	201 238	0.01	29	470	44	5	4	13	0.01	< 10	< 10	16	< 10	682
24872	201 238	0.01	18	270	>10000	15	3	46	< 0.01	< 10	< 10	11	< 10	1640
24873	201 238	< 0.01	9	180	50	5	4	23	< 0.01	< 10	< 10	4	< 10	348
24874	201 238	0.01	23	510	196	< 5	7	10	0.03	< 10	< 10	31	< 10	488
24875	201 238	0.01	27	390	2510	10	5	12	0.03	< 10	< 10	33	< 10	3300

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 25-JUL-89
Invoice # : I-8920286
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920286

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T23566	205	238	1.16	2.2	75	40	< 0.5	2	0.48	< 0.5	11	22	1130	4.44	< 10	< 1	0.05	< 10	2.01	295	2
T23567	205	238	0.27	1.0	70	< 10	< 0.5	< 2	>15.00	28.0	7	5	77	0.94	< 10	< 1	0.01	< 10	10.45	1185	< 1
T23702	205	238	0.22	1.4	40	90	< 0.5	< 2	0.64	< 0.5	4	18	43	>15.00	< 10	< 1	0.08	10	0.49	>10000	14

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J 2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-B
Tot. Pages: 1
Date : 25-JUL-89
Invoice # : I-8920286
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920286

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T23566	205	238	< 0.01	30	50	144	< 5	< 1	2	0.06	< 10	< 10	7	< 10	242
T23567	205	238	< 0.01	1	30	210	< 5	< 1	19	< 0.01	< 10	< 10	2	10	>10000
T23702	205	238	< 0.01	7	< 10	10	35	3	13	< 0.01	< 10	< 10	6	< 10	152

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23320	201 238	1.41	0.6	40	130	1.5	< 2	0.58	< 0.5	21	22	49	4.80	< 10	< 1	0.14	30	0.69	1710	1
23321	201 238	1.98	0.8	80	80	1.0	< 2	3.33	< 0.5	35	19	49	5.78	10	< 1	0.13	< 10	3.03	1540	2
23322	201 238	1.95	0.8	45	90	1.0	< 2	4.97	< 0.5	35	17	51	4.75	10	< 1	0.19	< 10	4.00	1355	1
23323	201 238	1.38	0.8	35	160	1.5	< 2	0.88	0.5	15	24	22	4.39	< 10	< 1	0.16	30	0.66	2130	1
23324	201 238	1.53	1.0	20	140	1.5	< 2	0.85	0.5	18	28	49	4.78	< 10	1	0.34	40	0.96	2130	2
23325	201 238	0.91	1.2	25	160	1.5	< 2	1.46	0.5	14	15	39	5.00	< 10	< 1	0.14	30	0.64	3090	1
23326	201 238	1.99	1.4	25	120	1.5	< 2	1.52	< 0.5	17	23	50	4.63	10	< 1	0.65	30	1.90	1775	1
23327	203 238	1.06	1.4	20	200	2.0	< 2	1.33	< 0.5	22	22	64	5.28	< 10	< 1	0.35	30	0.63	3150	2
23328	201 238	1.55	0.8	10	100	1.5	< 2	0.90	< 0.5	14	18	50	5.17	< 10	< 1	0.40	40	1.08	1880	1
23329	201 238	1.25	0.6	25	120	1.5	< 2	0.96	< 0.5	12	20	50	4.97	< 10	< 1	0.22	30	0.62	2030	1
23330	201 238	0.74	0.8	20	100	1.0	< 2	1.46	< 0.5	13	11	57	4.26	< 10	< 1	0.13	20	0.46	2320	3
23331	201 238	1.19	0.6	15	110	1.5	< 2	0.63	< 0.5	12	19	41	4.93	< 10	< 1	0.11	30	0.48	2140	1
23333	201 238	1.00	0.4	30	100	1.0	< 2	0.87	< 0.5	27	20	36	6.68	< 10	< 1	0.06	20	0.43	4660	2
23334	201 238	2.10	0.8	30	60	1.5	< 2	2.86	0.5	30	52	164	5.03	10	< 1	0.09	< 10	3.77	2480	2
23335	201 238	2.35	0.4	20	120	1.5	< 2	0.33	< 0.5	15	43	44	4.43	< 10	< 1	0.07	20	1.84	1305	2
23336	201 238	1.19	0.8	155	150	1.5	< 2	0.84	< 0.5	27	24	42	7.77	< 10	< 1	0.05	20	0.84	3850	2
23337	201 238	0.23	1.2	80	40	0.5	< 2	8.93	< 0.5	21	5	22	5.03	< 10	< 1	0.02	< 10	5.36	4300	1
23338	201 238	0.81	3.4	45	60	0.5	< 2	6.14	3.0	23	21	64	3.70	< 10	< 1	0.09	< 10	4.08	1970	1
23339	201 238	1.66	0.8	35	100	1.5	< 2	1.67	< 0.5	24	46	99	6.13	10	< 1	0.09	20	1.94	3780	3
23340	201 238	1.74	0.4	20	140	1.0	< 2	0.46	< 0.5	23	41	54	6.67	< 10	< 1	0.07	30	0.86	4410	3
23341	201 238	2.88	0.8	10	100	1.0	2	0.76	< 0.5	13	43	16	3.29	10	< 1	0.09	30	3.91	1735	1
23342	201 238	1.32	0.6	15	150	1.5	< 2	0.81	< 0.5	13	22	24	4.50	< 10	< 1	0.10	30	0.49	1770	1
23343	201 238	1.15	0.8	30	100	1.5	< 2	0.74	< 0.5	13	19	21	5.16	< 10	< 1	0.09	30	0.42	1500	2
23344	201 238	1.01	1.2	15	90	1.0	< 2	0.70	0.5	20	17	31	4.13	< 10	< 1	0.13	30	0.39	2200	1
23345	201 238	0.80	0.8	15	80	0.5	< 2	2.08	0.5	17	15	36	3.83	< 10	< 1	0.11	20	1.28	1750	1
23346	201 238	0.86	0.8	15	80	1.5	< 2	1.09	0.5	14	14	33	4.00	< 10	< 1	0.12	30	0.68	1525	< 1
23347	201 238	0.82	0.6	20	80	1.0	< 2	1.81	< 0.5	15	13	35	3.92	< 10	< 1	0.11	20	1.22	1425	1
23348	201 238	0.47	0.6	10	50	0.5	< 2	7.33	1.5	11	8	20	2.68	< 10	< 1	0.09	< 10	4.37	1315	1
23349	201 238	0.32	0.6	20	50	0.5	< 2	10.90	< 0.5	12	6	22	2.26	< 10	< 1	0.05	< 10	6.47	1440	1
23350	201 238	0.39	0.6	5	50	0.5	< 2	9.59	0.5	12	8	24	2.52	< 10	< 1	0.06	< 10	5.52	1735	1
23351	201 238	0.25	0.6	10	40	0.5	< 2	13.25	< 0.5	12	5	18	2.22	< 10	< 1	0.04	< 10	7.58	1660	< 1
23352	201 238	0.33	0.6	10	50	0.5	< 2	10.50	< 0.5	11	7	19	3.37	< 10	< 1	0.05	< 10	6.00	2530	1
23353	201 238	0.46	0.8	15	60	0.5	< 2	9.19	< 0.5	17	8	30	3.08	< 10	< 1	0.10	< 10	5.37	1680	1
23354	201 238	0.43	0.6	10	40	0.5	< 2	9.17	0.5	13	6	22	2.98	< 10	< 1	0.08	< 10	5.28	1530	< 1
23355	201 238	0.33	1.2	20	60	1.0	< 2	13.60	< 0.5	14	5	22	4.52	< 10	< 1	0.08	< 10	7.52	4310	< 1
23356	201 238	0.63	1.0	30	80	0.5	< 2	7.75	< 0.5	14	7	22	4.60	< 10	< 1	0.21	< 10	4.66	3490	< 1
23357	201 238	1.11	1.2	20	110	1.5	< 2	7.46	< 0.5	15	14	152	5.00	< 10	< 1	0.30	< 10	4.79	3160	1
23358	201 238	1.50	0.4	15	150	1.5	< 2	0.37	< 0.5	25	22	22	4.30	< 10	< 1	0.19	30	0.68	1430	1
23385	201 238	0.40	20.6	30	70	0.5	2	2.71	3.5	16	6	40	4.50	< 10	< 1	0.14	10	1.68	3370	1
23386	201 238	0.82	2.2	10	110	1.5	< 2	1.30	1.5	14	12	83	6.02	< 10	1	0.16	40	0.87	2830	2

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23320	201 238	0.01	28	890	54	5	6	11	0.03	< 10	< 10	49	< 10	236
23321	201 238	0.01	42	1410	42	5	7	17	0.06	< 10	< 10	91	< 10	294
23322	201 238	0.01	34	1680	32	5	6	25	0.10	< 10	< 10	89	< 10	550
23323	201 238	0.01	26	950	40	5	4	11	0.03	< 10	< 10	40	< 10	564
23324	201 238	0.01	30	830	58	< 5	6	13	0.04	< 10	< 10	38	< 10	442
23325	201 238	0.01	19	1070	100	5	4	14	0.02	< 10	< 10	25	< 10	384
23326	201 238	0.01	26	920	122	5	7	12	0.03	< 10	< 10	34	< 10	612
23327	203 238	0.01	24	1020	152	5	5	11	0.01	< 10	< 10	22	< 10	552
23328	201 238	0.01	23	1090	78	5	6	11	0.02	< 10	< 10	24	< 10	220
23329	201 238	< 0.01	20	1140	70	5	6	12	0.02	< 10	< 10	31	< 10	264
23330	201 238	0.01	17	1630	56	< 5	4	12	0.01	< 10	< 10	17	< 10	296
23331	201 238	0.01	19	1220	70	< 5	5	11	0.02	< 10	< 10	31	< 10	366
23333	201 238	< 0.01	29	950	62	5	6	12	0.01	< 10	< 10	40	< 10	158
23334	201 238	0.01	45	700	126	< 5	9	16	0.06	< 10	< 10	68	< 10	720
23335	201 238	< 0.01	23	770	110	< 5	6	9	0.06	< 10	< 10	60	< 10	618
23336	201 238	< 0.01	46	670	70	10	5	9	0.02	< 10	< 10	47	< 10	200
23337	201 238	0.01	27	480	28	10	6	29	< 0.01	< 10	< 10	23	< 10	54
23338	201 238	0.01	26	840	1400	10	5	26	0.03	< 10	< 10	34	< 10	2240
23339	201 238	0.01	46	1020	80	5	9	17	0.04	< 10	< 10	70	< 10	370
23340	201 238	< 0.01	36	1310	50	< 5	7	11	0.02	< 10	< 10	73	< 10	208
23341	201 238	< 0.01	15	430	32	< 5	5	9	0.15	< 10	< 10	49	< 10	510
23342	201 238	< 0.01	21	1410	68	5	5	20	0.02	< 10	< 10	43	< 10	340
23343	201 238	0.01	21	1120	86	5	6	22	0.02	< 10	< 10	41	< 10	324
23344	201 238	< 0.01	25	880	242	5	7	13	0.01	< 10	< 10	36	< 10	616
23345	201 238	0.01	27	750	184	5	8	19	0.02	< 10	< 10	30	< 10	532
23346	201 238	< 0.01	22	800	138	5	7	14	0.02	< 10	< 10	27	< 10	506
23347	201 238	< 0.01	18	670	122	5	7	16	0.02	< 10	< 10	26	< 10	472
23348	201 238	0.01	12	560	84	5	5	31	0.01	< 10	< 10	16	< 10	1080
23349	201 238	0.01	10	420	76	< 5	4	20	0.01	< 10	< 10	13	< 10	330
23350	201 238	0.01	13	430	90	5	4	21	0.01	< 10	< 10	15	< 10	436
23351	201 238	0.01	9	350	92	5	3	21	< 0.01	< 10	< 10	11	< 10	176
23352	201 238	0.01	11	380	32	5	5	31	0.01	< 10	< 10	16	< 10	226
23353	201 238	0.01	20	590	80	5	4	26	0.02	< 10	< 10	18	< 10	290
23354	201 238	0.01	12	750	58	5	4	23	0.01	< 10	< 10	16	< 10	344
23355	201 238	0.01	16	340	52	5	7	36	< 0.01	< 10	< 10	15	< 10	188
23356	201 238	0.01	43	420	52	5	10	15	< 0.01	< 10	< 10	11	< 10	160
23357	201 238	0.01	37	500	104	5	11	15	0.01	< 10	< 10	16	< 10	102
23358	201 238	0.01	35	410	84	5	10	12	0.05	< 10	< 10	36	< 10	88
23385	201 238	< 0.01	13	410	>10000	25	6	9	< 0.01	< 10	< 10	9	< 10	1710
23386	201 238	0.01	19	820	612	5	7	12	0.01	< 10	< 10	21	< 10	1010

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page No. : 2-A
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23387	201 238	0.39	13.0	40	30	0.5	< 2	6.37	38.0	17	6	164	3.79	< 10	3	0.03	< 10	3.82	1885	1
23388	201 238	0.41	6.6	30	80	0.5	< 2	1.04	3.0	12	6	25	2.73	< 10	< 1	0.05	20	0.51	1575	1
23389	217 238	0.24	34.4	40	20	< 0.5	4	6.36	4.5	8	95	20	1.94	< 10	< 1	0.13	< 10	3.73	1445	< 1
23390	201 238	0.29	7.8	30	40	0.5	< 2	9.56	8.5	14	6	69	2.65	< 10	< 1	0.04	< 10	5.45	1850	1
23391	201 238	1.05	2.4	25	80	1.0	< 2	0.16	3.0	20	11	33	4.08	< 10	< 1	0.33	40	0.73	1980	1
23392	201 238	1.24	2.0	35	70	1.0	< 2	3.34	3.0	17	16	40	3.84	< 10	< 1	0.16	< 10	2.93	2510	1
23393	201 238	1.38	2.4	25	110	1.0	< 2	0.50	2.0	20	21	53	3.89	< 10	< 1	0.25	30	0.77	1690	1
23394	201 238	2.39	1.2	10	80	1.0	< 2	0.58	1.0	22	47	98	5.08	< 10	< 1	0.19	30	2.13	990	1
23395	201 238	0.42	2.4	15	40	< 0.5	< 2	11.15	1.0	15	6	290	2.17	< 10	< 1	0.10	< 10	6.57	1705	< 1
23396	201 238	1.39	2.6	20	80	0.5	< 2	2.34	1.0	16	23	182	3.75	< 10	< 1	0.20	20	2.11	1370	1
23397	201 238	0.71	1.2	10	50	< 0.5	< 2	8.44	1.0	13	14	34	2.45	< 10	< 1	0.07	< 10	5.24	1075	1
23398	201 238	0.54	1.4	40	40	< 0.5	< 2	9.97	1.5	16	11	37	3.68	< 10	< 1	0.06	< 10	5.74	2000	< 1
23399	201 238	0.85	1.4	25	90	< 0.5	< 2	5.44	1.5	19	16	46	4.97	< 10	< 1	0.09	< 10	3.38	3770	1
23400	201 238	1.24	0.8	< 5	140	0.5	< 2	2.53	1.5	12	21	25	4.19	< 10	< 1	0.10	10	1.58	2260	< 1
23401	201 238	0.61	0.4	25	100	< 0.5	< 2	1.30	0.5	15	10	42	5.62	< 10	2	0.07	20	0.78	2940	1
23402	201 238	1.09	0.4	15	130	< 0.5	< 2	1.88	0.5	16	22	44	3.83	< 10	< 1	0.08	20	1.37	1620	1
23403	201 238	1.27	0.6	20	120	0.5	< 2	0.87	< 0.5	14	22	39	4.39	< 10	< 1	0.10	30	0.58	1630	1
23404	201 238	1.17	0.6	15	160	< 0.5	< 2	2.11	< 0.5	22	22	54	5.04	< 10	< 1	0.12	20	1.35	3730	2
23405	201 238	1.26	0.2	25	170	< 0.5	< 2	0.79	< 0.5	16	23	71	5.82	< 10	< 1	0.12	30	0.98	4550	2
23406	201 238	1.30	0.2	15	190	< 0.5	< 2	0.54	< 0.5	12	20	12	4.28	< 10	< 1	0.09	20	0.59	2800	2
23407	201 238	1.33	0.4	15	190	< 0.5	< 2	0.62	< 0.5	12	22	21	5.89	< 10	< 1	0.07	20	0.57	3830	3
23408	201 238	1.57	0.6	25	90	< 0.5	< 2	0.83	< 0.5	22	40	73	5.58	< 10	< 1	0.08	20	1.36	2800	3
23409	201 238	1.34	0.4	30	90	< 0.5	< 2	2.34	< 0.5	17	32	62	4.67	< 10	1	0.06	10	2.10	2540	2
23410	201 238	1.30	0.4	25	100	< 0.5	< 2	2.21	< 0.5	14	27	55	5.85	< 10	< 1	0.11	20	1.92	3100	3
23413	201 238	2.48	0.2	15	190	< 0.5	< 2	0.34	< 0.5	11	45	30	4.53	< 10	< 1	0.08	20	0.74	1140	< 1
23414	201 238	2.10	1.8	90	210	< 0.5	4	0.45	< 0.5	38	36	53	8.01	< 10	< 1	0.10	30	0.61	2440	2
23415	201 238	1.62	0.4	15	200	< 0.5	< 2	0.61	< 0.5	13	27	26	6.43	< 10	< 1	0.09	30	0.76	5010	2
23416	201 238	1.48	0.4	25	160	< 0.5	< 2	0.85	< 0.5	16	35	33	6.60	< 10	1	0.05	20	0.75	4690	3
23417	201 238	1.74	0.2	25	110	< 0.5	< 2	0.46	< 0.5	19	44	54	5.96	< 10	< 1	0.06	20	1.01	2990	3
23418	201 238	1.73	< 0.2	25	170	< 0.5	< 2	0.57	< 0.5	17	37	36	7.53	< 10	< 1	0.05	20	0.66	5190	3
23419	201 238	2.14	0.4	25	150	< 0.5	< 2	0.56	< 0.5	23	60	71	7.96	< 10	< 1	0.07	30	1.31	4830	3
23420	201 238	2.08	< 0.2	15	220	< 0.5	< 2	0.40	< 0.5	10	30	15	5.24	< 10	< 1	0.06	20	0.59	2270	2
23421	201 238	1.33	0.8	30	130	< 0.5	< 2	1.17	< 0.5	12	21	34	4.65	< 10	< 1	0.09	20	0.52	2280	1
23422	201 238	1.57	0.6	20	140	< 0.5	< 2	0.58	0.5	12	26	30	4.82	< 10	1	0.07	30	0.51	1485	1
23423	201 238	0.93	2.6	20	80	< 0.5	< 2	3.99	5.5	16	19	80	4.62	< 10	< 1	0.07	< 10	2.65	2790	1
23424	201 238	0.73	2.4	25	70	< 0.5	< 2	6.34	6.0	18	15	83	4.26	< 10	< 1	0.06	< 10	3.97	2720	1
23425	201 238	0.69	1.0	20	70	< 0.5	< 2	2.96	1.0	12	12	37	3.96	< 10	1	0.06	< 10	1.92	1930	1
23465	201 238	2.16	1.6	25	170	< 0.5	< 2	0.62	< 0.5	14	42	63	4.96	< 10	< 1	0.08	30	0.75	2290	2
23466	201 238	1.79	1.2	30	100	< 0.5	< 2	0.92	< 0.5	17	47	71	5.45	< 10	< 1	0.09	20	1.06	2540	2
23467	201 238	2.22	0.6	30	150	< 0.5	< 2	0.82	< 0.5	16	38	33	6.20	< 10	< 1	0.10	30	0.81	3490	3

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23387	201	238	0.01	18	430	>10000	15	4	16	0.01	< 10	< 10	14	20	>10000
23388	201	238	< 0.01	16	790	5260	10	5	7	< 0.01	< 10	< 10	12	< 10	2140
23389	217	238	0.01	9	260	>10000	30	2	18	< 0.01	< 10	< 10	6	< 10	2350
23390	201	238	0.01	13	400	5390	20	4	27	0.01	< 10	< 10	11	< 10	4340
23391	201	238	< 0.01	27	410	1520	5	5	4	0.01	< 10	< 10	12	< 10	1830
23392	201	238	0.01	24	810	1360	5	6	9	0.01	< 10	< 10	25	< 10	1930
23393	201	238	0.01	28	780	1305	5	8	14	0.04	< 10	< 10	40	< 10	2100
23394	201	238	0.01	32	570	504	5	12	12	0.14	< 10	< 10	109	< 10	942
23395	201	238	0.01	11	520	440	10	4	16	0.01	< 10	< 10	14	< 10	614
23396	201	238	0.01	23	770	592	5	7	14	0.05	< 10	< 10	47	< 10	1005
23397	201	238	0.01	16	570	706	5	4	21	0.03	< 10	< 10	30	< 10	974
23398	201	238	0.01	22	550	398	10	5	30	0.01	< 10	< 10	20	< 10	2040
23399	201	238	0.01	24	620	328	10	7	22	0.02	< 10	< 10	28	< 10	1285
23400	201	238	0.01	19	840	162	5	6	24	0.03	< 10	< 10	39	< 10	554
23401	201	238	< 0.01	23	930	138	5	5	16	0.01	< 10	< 10	21	< 10	478
23402	201	238	0.01	26	730	188	5	6	21	0.04	< 10	< 10	38	< 10	602
23403	201	238	0.01	22	900	214	< 5	6	19	0.03	< 10	< 10	40	< 10	666
23404	201	238	0.01	27	1030	106	5	7	24	0.05	< 10	< 10	46	< 10	288
23405	201	238	< 0.01	29	1100	30	< 5	7	10	0.02	< 10	< 10	47	< 10	278
23406	201	238	< 0.01	17	1020	22	< 5	4	12	0.04	< 10	< 10	60	< 10	126
23407	201	238	< 0.01	22	1380	16	< 5	6	11	0.02	< 10	< 10	54	< 10	110
23408	201	238	0.01	39	1000	44	5	9	16	0.06	< 10	< 10	58	< 10	270
23409	201	238	0.01	32	990	18	5	7	19	0.05	< 10	< 10	48	< 10	254
23410	201	238	0.01	34	940	26	5	9	15	0.04	< 10	< 10	47	< 10	232
23413	201	238	0.01	22	590	18	< 5	6	15	0.06	< 10	< 10	75	< 10	150
23414	201	238	0.01	51	980	58	10	8	14	0.05	< 10	< 10	72	< 10	164
23415	201	238	< 0.01	25	1510	18	< 5	7	10	0.03	< 10	< 10	60	< 10	204
23416	201	238	< 0.01	29	1510	28	< 5	7	12	0.02	< 10	< 10	55	< 10	210
23417	201	238	< 0.01	33	1100	42	< 5	7	10	0.02	< 10	< 10	63	< 10	242
23418	201	238	< 0.01	26	1720	60	5	6	10	0.01	< 10	< 10	57	< 10	226
23419	201	238	< 0.01	48	1110	66	< 5	15	8	0.02	< 10	< 10	80	< 10	292
23420	201	238	< 0.01	19	920	202	< 5	3	13	0.03	< 10	< 10	67	< 10	300
23421	201	238	< 0.01	17	1400	270	< 5	4	29	0.02	< 10	< 10	35	< 10	690
23422	201	238	0.01	22	880	216	< 5	7	18	0.03	< 10	< 10	49	< 10	624
23423	201	238	0.01	25	630	1620	5	6	21	0.02	< 10	< 10	33	< 10	3530
23424	201	238	0.01	23	550	1425	5	6	36	0.01	< 10	< 10	29	< 10	4280
23425	201	238	0.01	16	700	328	5	5	15	0.01	< 10	< 10	23	< 10	1015
23465	201	238	< 0.01	28	1540	116	< 5	7	16	0.03	< 10	< 10	54	< 10	328
23466	201	238	0.01	28	1100	76	5	8	16	0.04	< 10	< 10	55	< 10	588
23467	201	238	< 0.01	29	1310	150	< 5	7	14	0.04	< 10	< 10	78	< 10	336

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 1S9

Project : BLENDE
Comments :

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23468	201 238	2.32	1.2	55	200	1.5	< 2	0.52	< 0.5	24	49	49	6.88	< 10	< 1	0.06	30	0.90	3600	2
23469	201 238	1.09	3.0	60	80	1.0	< 2	4.70	1.0	71	25	239	6.33	< 10	< 1	0.08	< 10	2.57	3270	1
23470	201 238	1.20	1.2	40	60	1.0	< 2	5.12	< 0.5	23	28	59	3.81	< 10	3	0.11	< 10	3.55	1670	2
23471	201 238	1.83	1.0	40	120	1.0	< 2	2.52	< 0.5	28	51	83	5.86	< 10	< 1	0.11	10	2.51	3060	3
23472	201 238	1.72	0.6	35	170	1.0	< 2	0.70	< 0.5	15	27	18	4.86	< 10	< 1	0.11	20	1.36	3560	3
23473	201 238	1.66	2.6	40	140	1.0	< 2	0.58	1.0	22	29	71	5.40	< 10	< 1	0.14	30	0.95	3070	1
23474	201 238	1.39	1.4	40	130	1.0	< 2	0.95	0.5	15	23	31	4.62	< 10	1	0.07	30	0.76	2410	1
23475	201 238	1.63	1.6	25	190	1.0	< 2	1.15	1.5	15	25	21	5.36	< 10	< 1	0.05	20	0.79	3610	1
23476	201 238	0.67	1.8	30	100	0.5	< 2	6.67	1.0	18	12	31	3.71	< 10	< 1	0.05	< 10	4.26	2700	1
23477	201 238	0.91	1.0	20	70	1.0	< 2	0.83	0.5	20	16	109	3.82	< 10	< 1	0.09	20	0.49	685	1
23478	201 238	1.08	1.2	25	100	1.0	< 2	0.81	0.5	28	20	99	4.36	< 10	< 1	0.10	30	0.79	1650	1
23479	201 238	1.38	1.4	35	100	1.0	< 2	0.61	0.5	30	25	162	5.47	< 10	< 1	0.15	30	0.83	2070	1
23480	201 238	1.09	2.2	35	90	1.0	< 2	3.73	0.5	27	19	98	4.90	< 10	1	0.13	< 10	2.77	2720	< 1
23481	201 238	0.74	1.6	30	110	1.0	< 2	5.19	1.0	14	13	26	3.80	< 10	< 1	0.10	< 10	3.36	2810	1
23482	201 238	1.56	2.0	30	110	1.0	< 2	0.96	2.0	24	24	72	5.00	< 10	< 1	0.14	30	1.44	1865	1
23483	201 238	0.72	1.8	30	70	1.0	< 2	2.96	0.5	19	13	43	3.52	< 10	< 1	0.10	10	2.07	1475	1
23484	201 238	0.52	1.2	20	60	1.0	< 2	3.92	1.5	17	11	29	2.80	< 10	< 1	0.11	< 10	2.71	1370	1
23485	201 238	0.40	2.0	30	40	1.0	< 2	6.31	2.0	20	8	33	2.80	< 10	< 1	0.08	< 10	4.19	1505	1
23486	201 238	0.70	2.0	30	60	1.0	< 2	3.18	0.5	20	12	42	3.22	< 10	< 1	0.10	< 10	2.48	1340	1
23487	201 238	0.57	1.6	20	60	1.0	< 2	4.73	< 0.5	16	10	36	3.09	< 10	1	0.07	< 10	3.35	1430	1
23488	201 238	0.24	2.0	25	50	0.5	< 2	8.26	0.5	16	4	121	2.42	< 10	< 1	0.07	< 10	4.72	1180	1
23489	201 238	0.45	1.2	25	70	0.5	< 2	7.75	< 0.5	16	7	36	2.86	< 10	< 1	0.07	< 10	4.67	1690	< 1
23490	201 238	0.87	1.2	30	110	0.5	< 2	1.89	< 0.5	15	16	45	3.46	< 10	< 1	0.11	10	1.27	1775	< 1
23541	201 238	0.39	0.8	30	80	0.5	2	12.65	< 0.5	14	6	12	3.06	< 10	< 1	0.05	< 10	7.10	2640	< 1
23542	201 238	0.28	0.8	30	50	0.5	< 2	13.25	< 0.5	13	4	10	2.97	< 10	< 1	0.03	< 10	7.37	2670	< 1
23543	201 238	0.35	0.8	40	70	0.5	2	11.95	< 0.5	15	5	13	3.19	< 10	< 1	0.04	< 10	6.77	2360	< 1
23544	201 238	0.87	0.8	45	120	2.0	< 2	3.40	< 0.5	19	13	23	4.40	< 10	< 1	0.10	< 10	2.04	2800	1
23545	201 238	0.24	0.6	25	50	0.5	< 2	14.05	< 0.5	13	3	9	3.15	< 10	< 1	0.05	< 10	7.87	2580	< 1
23546	201 238	0.95	1.0	25	110	2.0	< 2	4.32	< 0.5	18	11	17	5.90	< 10	< 1	0.25	< 10	2.76	3220	< 1
23547	201 238	0.55	0.6	25	80	0.5	2	8.50	< 0.5	14	9	18	3.15	< 10	< 1	0.07	< 10	4.98	2180	< 1
23548	201 238	0.60	0.6	25	80	0.5	2	7.20	< 0.5	14	11	17	3.33	< 10	< 1	0.08	< 10	4.28	2180	< 1
23549	201 238	0.38	0.8	30	50	< 0.5	< 2	9.96	< 0.5	16	7	23	2.56	< 10	< 1	0.05	< 10	5.79	1615	< 1
23672	201 238	0.80	0.8	15	90	1.0	< 2	0.99	< 0.5	16	13	56	4.84	< 10	1	0.13	20	0.47	3210	1
23673	201 238	0.68	0.8	25	80	1.0	4	1.44	< 0.5	19	11	72	4.90	< 10	< 1	0.10	20	0.80	2630	2
23674	201 238	1.07	0.6	30	110	1.0	< 2	1.41	< 0.5	16	17	46	4.26	< 10	< 1	0.23	30	1.02	2180	1
23675	201 238	2.37	0.6	25	120	1.5	6	0.87	< 0.5	25	31	51	6.45	10	1	0.19	20	2.01	2240	1
23689	201 238	0.58	12.8	50	30	0.5	4	7.83	12.5	24	8	48	3.64	< 10	2	0.15	< 10	4.60	1220	< 1
23690	201 238	0.34	25.2	65	20	0.5	4	8.34	14.5	24	8	54	2.90	< 10	< 1	0.06	< 10	4.88	975	< 1
23691	201 238	0.31	42.6	65	20	0.5	6	10.20	23.0	18	8	63	2.86	< 10	3	0.05	< 10	5.93	1110	< 1
23692	201 238	0.13	41.0	115	10	0.5	6	12.60	24.5	18	3	96	3.93	< 10	< 1	0.02	< 10	7.09	1805	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23468	201 238	< 0.01	37	840	76	5	11	11	0.04	< 10	< 10	65	< 10	644
23469	201 238	0.01	75	1080	758	10	10	27	0.02	< 10	< 10	46	< 10	1710
23470	201 238	0.01	38	1080	118	5	5	31	0.06	< 10	< 10	42	< 10	436
23471	201 238	0.01	49	1110	54	< 5	9	20	0.05	< 10	< 10	68	< 10	350
23472	201 238	< 0.01	23	1360	28	< 5	4	12	0.02	< 10	< 10	68	< 10	130
23473	201 238	0.01	35	900	1570	< 5	10	17	0.04	< 10	< 10	51	< 10	1420
23474	201 238	< 0.01	22	880	780	< 5	7	16	0.03	< 10	< 10	39	< 10	814
23475	201 238	0.01	19	1040	1550	< 5	7	15	0.03	< 10	< 10	48	< 10	862
23476	201 238	0.01	20	680	692	5	6	61	0.02	< 10	< 10	23	< 10	718
23477	201 238	< 0.01	35	1020	168	< 5	6	11	0.01	< 10	< 10	29	< 10	732
23478	201 238	0.01	41	820	208	5	7	13	0.02	< 10	< 10	36	< 10	586
23479	201 238	< 0.01	46	770	368	5	12	9	0.01	< 10	< 10	59	< 10	690
23480	201 238	0.01	29	930	518	5	9	16	0.01	< 10	< 10	37	< 10	800
23481	201 238	0.01	14	810	280	5	5	14	0.02	< 10	< 10	22	< 10	870
23482	201 238	0.01	29	610	602	< 5	9	11	0.04	< 10	< 10	38	< 10	2060
23483	201 238	0.01	22	820	492	5	5	14	0.02	< 10	< 10	22	< 10	824
23484	201 238	0.01	20	770	462	5	4	17	0.02	< 10	< 10	18	< 10	854
23485	201 238	0.01	20	670	882	5	5	20	0.01	< 10	< 10	12	< 10	1550
23486	201 238	0.01	24	560	706	5	5	10	0.02	< 10	< 10	17	< 10	914
23487	201 238	0.01	18	590	198	5	4	12	0.01	< 10	< 10	15	< 10	380
23488	201 238	0.01	11	700	88	25	3	24	< 0.01	< 10	< 10	9	< 10	380
23489	201 238	0.01	14	470	132	5	4	15	0.01	< 10	< 10	15	< 10	260
23490	201 238	0.01	22	680	146	5	5	15	0.04	< 10	< 10	30	< 10	308
23541	201 238	0.01	13	460	26	5	4	20	0.01	< 10	< 10	16	< 10	142
23542	201 238	0.01	10	340	14	5	3	19	0.01	< 10	< 10	12	< 10	92
23543	201 238	0.01	13	410	34	5	3	18	0.01	< 10	< 10	14	< 10	180
23544	201 238	0.01	21	790	32	5	7	14	0.03	< 10	< 10	27	< 10	220
23545	201 238	0.01	8	460	16	5	4	25	< 0.01	< 10	< 10	7	< 10	146
23546	201 238	0.01	23	760	66	5	10	13	0.01	< 10	< 10	16	< 10	344
23547	201 238	0.01	15	500	50	5	4	31	0.02	< 10	< 10	18	< 10	434
23548	201 238	0.01	15	510	34	5	5	24	0.03	< 10	< 10	23	< 10	226
23549	201 238	0.01	15	550	68	5	4	45	0.02	< 10	< 10	16	< 10	360
23672	201 238	0.01	21	1080	42	5	6	16	0.01	< 10	< 10	16	< 10	198
23673	201 238	< 0.01	20	850	32	5	6	16	0.02	< 10	< 10	18	< 10	152
23674	201 238	0.01	24	860	34	5	7	18	0.03	< 10	< 10	25	< 10	448
23675	201 238	0.01	29	900	52	< 5	13	18	0.22	< 10	< 10	102	< 10	590
23689	201 238	0.01	27	980	5690	15	6	22	0.01	< 10	< 10	23	10	7630
23690	201 238	0.01	26	470	>10000	95	4	24	0.01	< 10	< 10	12	10	>10000
23691	201 238	0.01	21	440	>10000	110	3	23	0.01	< 10	< 10	11	20	>10000
23692	201 238	0.01	20	240	>10000	70	2	25	< 0.01	< 10	< 10	5	20	>10000

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page No. : 4-A
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23693	201 238	0.56	21.2	445	70	1.0	2	6.14	4.5	39	12	90	14.10	10	< 1	0.05	< 10	3.65	2280	4
23694	201 238	1.02	9.4	75	70	< 0.5	< 2	5.89	8.0	36	15	64	5.75	< 10	< 1	0.21	< 10	3.90	3050	1
23695	201 238	0.36	7.2	40	20	< 0.5	2	10.55	11.5	16	7	42	2.89	< 10	< 1	0.05	< 10	6.30	1510	< 1
23696	201 238	0.48	7.0	70	30	< 0.5	2	5.12	13.5	20	8	48	4.38	< 10	< 1	0.07	< 10	3.20	1685	< 1
23703	201 238	1.33	0.6	30	170	1.5	< 2	0.91	< 0.5	14	24	32	4.41	< 10	< 1	0.07	20	0.59	1710	2
23704	201 238	1.45	0.4	35	200	1.5	< 2	0.42	< 0.5	18	24	35	5.38	< 10	< 1	0.09	30	0.56	2260	3
23723	201 238	1.11	0.6	15	140	0.5	< 2	2.20	< 0.5	11	27	20	2.53	< 10	< 1	0.12	< 10	0.78	1545	1
23724	201 238	2.22	0.4	45	170	1.5	< 2	0.42	< 0.5	13	35	19	4.77	< 10	< 1	0.17	30	0.87	1310	2
23725	201 238	1.87	0.8	40	180	1.0	< 2	1.13	< 0.5	17	32	28	4.32	10	< 1	0.22	20	0.95	1810	1
23726	201 238	1.32	0.6	20	130	1.0	2	2.00	< 0.5	15	15	21	2.82	< 10	1	0.29	< 10	0.94	1465	< 1
23727	201 238	1.82	0.2	25	100	1.0	2	0.38	1.5	14	31	18	4.49	< 10	< 1	0.18	20	0.77	1550	1
23728	201 238	1.83	0.4	15	140	1.0	< 2	1.09	< 0.5	14	29	23	3.55	< 10	< 1	0.34	20	1.38	1305	1
23729	201 238	1.52	0.6	25	170	0.5	2	1.73	< 0.5	21	25	45	3.00	< 10	< 1	0.25	10	1.46	1005	1
23730	201 238	1.42	0.6	30	80	0.5	< 2	0.95	0.5	15	20	44	3.55	< 10	< 1	0.18	20	1.20	650	2
23731	201 238	1.72	1.8	40	120	1.0	< 2	0.95	1.5	16	26	32	4.44	< 10	< 1	0.23	20	1.25	1285	2
23732	201 238	1.79	1.0	45	150	1.5	< 2	0.75	1.0	17	30	32	4.88	< 10	< 1	0.20	20	0.92	1860	2
23792	201 238	1.21	1.8	110	140	1.5	4	2.71	1.5	28	23	55	6.36	< 10	< 1	0.13	< 10	1.92	2440	4
23793	201 238	0.96	9.2	335	80	0.5	2	5.46	23.5	45	20	103	10.20	< 10	< 1	0.10	< 10	3.39	2230	3
23794	201 238	1.09	5.2	200	60	1.0	2	5.25	25.0	27	16	57	5.81	< 10	< 1	0.12	< 10	3.82	1290	3
23795	201 238	0.80	14.6	230	50	1.0	4	6.32	43.0	22	18	59	5.85	< 10	2	0.11	< 10	3.96	1680	1
23796	201 238	0.97	9.4	300	80	1.5	6	2.79	42.0	29	23	71	8.44	< 10	< 1	0.14	< 10	1.71	1595	4
23797	201 238	0.43	4.0	160	30	0.5	6	10.65	30.0	21	14	35	4.32	< 10	< 1	0.04	< 10	6.17	2720	2
23798	201 238	1.08	6.2	175	70	1.5	2	1.52	30.5	21	17	64	6.28	< 10	1	0.09	10	0.87	1875	3
23800	201 238	0.56	2.2	115	60	1.0	2	6.91	13.5	21	13	31	4.64	< 10	< 1	0.06	< 10	4.03	3090	1
23801	201 238	0.61	1.2	90	80	0.5	6	8.59	1.5	22	13	34	4.44	< 10	< 1	0.08	< 10	5.20	1955	1
23802	201 238	0.57	2.0	30	80	1.5	< 2	3.33	0.5	18	11	31	5.48	< 10	< 1	0.09	< 10	1.62	3400	1
23819	201 238	1.05	1.8	85	180	2.0	< 2	0.21	0.5	21	18	144	6.22	< 10	< 1	0.18	30	0.22	1890	27
23820	201 238	0.85	0.8	60	180	2.0	< 2	0.30	< 0.5	25	12	90	4.71	< 10	< 1	0.27	40	0.18	2160	28
23821	217 238	1.12	0.6	40	190	1.0	< 2	0.21	< 0.5	12	78	40	2.03	< 10	< 1	0.56	30	0.17	1405	17
23822	201 238	0.30	0.8	25	100	1.0	< 2	14.90	< 0.5	12	5	37	3.74	< 10	< 1	0.03	< 10	8.44	4000	1
23823	201 238	0.25	0.6	20	90	0.5	2	>15.00	< 0.5	13	3	35	3.86	< 10	< 1	0.03	< 10	8.52	4230	5
23824	201 238	0.16	0.8	40	380	0.5	2	>15.00	< 0.5	15	4	74	3.85	< 10	< 1	0.01	< 10	9.49	4380	3
23825	201 238	0.18	0.8	25	160	1.0	< 2	>15.00	< 0.5	12	3	73	3.65	< 10	< 1	0.01	< 10	9.03	4420	2
23826	201 238	0.28	1.0	30	280	0.5	4	13.85	< 0.5	13	5	131	4.33	< 10	< 1	0.02	< 10	7.84	4870	4
23827	201 238	0.66	1.0	30	220	1.5	4	8.47	< 0.5	15	13	163	5.55	< 10	1	0.06	< 10	4.82	5380	2
23828	201 238	0.46	0.6	30	110	1.0	2	12.80	< 0.5	15	13	52	3.79	< 10	< 1	0.05	< 10	7.34	3430	1
23829	201 238	0.38	0.6	35	110	1.0	< 2	13.15	< 0.5	13	9	41	3.68	< 10	< 1	0.04	< 10	7.26	3500	1
23830	201 238	1.04	1.2	30	210	2.5	4	5.77	< 0.5	15	22	51	6.50	< 10	< 1	0.07	< 10	3.16	6370	2
23831	201 238	0.21	0.8	30	70	1.0	2	13.60	< 0.5	12	3	18	3.36	< 10	< 1	0.03	< 10	7.73	3780	1
23832	201 238	1.25	1.0	45	230	3.0	< 2	2.31	< 0.5	18	22	48	7.55	10	< 1	0.09	10	1.29	5860	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23693	201 238	0.01	91	320	1260	60	4	11	0.03	< 10	< 10	20	20	3980
23694	201 238	0.01	42	570	>10000	15	9	13	0.03	< 10	< 10	21	10	4370
23695	201 238	0.01	16	310	4910	15	3	20	0.01	< 10	< 10	12	10	6960
23696	201 238	0.01	27	600	4050	15	6	12	0.01	< 10	< 10	14	10	7180
23703	201 238	< 0.01	22	690	116	< 5	5	12	0.02	< 10	< 10	37	< 10	350
23704	201 238	< 0.01	26	980	84	< 5	5	9	0.01	< 10	< 10	39	< 10	302
23723	201 238	0.01	20	940	48	< 5	3	19	0.01	< 10	< 10	21	< 10	210
23724	201 238	0.01	25	510	48	< 5	8	13	0.04	< 10	< 10	54	< 10	288
23725	201 238	0.01	28	880	54	< 5	6	17	0.04	< 10	< 10	44	< 10	764
23726	201 238	0.01	15	1010	64	< 5	4	19	0.02	< 10	< 10	22	< 10	286
23727	201 238	0.01	22	420	242	< 5	5	9	0.03	< 10	< 10	40	< 10	886
23728	201 238	0.01	27	750	70	< 5	5	13	0.03	< 10	< 10	34	< 10	274
23729	201 238	0.01	25	800	98	5	5	21	0.05	< 10	< 10	38	< 10	274
23730	201 238	0.01	24	840	228	< 5	5	14	0.02	< 10	< 10	28	< 10	910
23731	201 238	0.01	27	840	1160	5	6	12	0.03	< 10	< 10	35	< 10	1450
23732	201 238	0.01	28	910	308	5	6	12	0.03	< 10	< 10	40	< 10	1350
23792	201 238	0.01	53	580	138	10	8	13	0.03	< 10	< 10	36	< 10	2090
23793	201 238	0.01	78	440	4390	25	6	19	0.02	< 10	< 10	36	10	>10000
23794	201 238	0.01	41	440	1210	10	5	22	0.02	< 10	< 10	24	10	>10000
23795	201 238	0.01	43	660	5510	15	3	16	0.01	< 10	< 10	18	10	>10000
23796	201 238	0.01	55	700	2610	25	4	12	0.01	< 10	< 10	22	< 10	>10000
23797	201 238	0.01	36	570	1045	5	2	12	< 0.01	< 10	< 10	13	10	>10000
23798	201 238	0.01	44	890	1575	10	4	10	0.02	< 10	< 10	28	< 10	>10000
23800	201 238	0.01	36	650	670	10	3	13	< 0.01	< 10	< 10	19	< 10	5650
23801	201 238	0.01	38	420	230	10	4	20	0.01	< 10	< 10	17	< 10	1975
23802	201 238	< 0.01	20	710	506	10	5	27	0.01	< 10	< 10	14	< 10	628
23819	201 238	< 0.01	91	1910	60	15	2	29	0.01	< 10	< 10	31	< 10	942
23820	201 238	< 0.01	81	1680	52	10	4	26	0.01	< 10	< 10	29	< 10	576
23821	217 238	0.01	38	1850	380	5	< 1	8	< 0.01	< 10	< 10	44	< 10	180
23822	201 238	0.01	12	310	8	10	1	27	0.01	< 10	< 10	12	< 10	98
23823	201 238	0.01	17	280	14	5	2	22	< 0.01	< 10	< 10	11	< 10	142
23824	201 238	0.01	14	230	18	5	2	35	< 0.01	< 10	< 10	10	< 10	156
23825	201 238	0.01	9	300	32	5	2	31	< 0.01	< 10	< 10	11	< 10	152
23826	201 238	0.01	14	390	46	5	2	25	< 0.01	< 10	< 10	18	< 10	238
23827	201 238	0.01	18	970	36	10	4	19	0.01	< 10	< 10	27	< 10	212
23828	201 238	0.01	18	550	30	5	5	22	0.01	< 10	< 10	24	< 10	138
23829	201 238	0.01	23	430	20	5	3	20	0.01	< 10	< 10	15	< 10	130
23830	201 238	0.01	27	1370	34	5	3	17	0.01	< 10	< 10	29	< 10	276
23831	201 238	0.01	15	600	24	5	2	24	< 0.01	< 10	< 10	8	< 10	110
23832	201 238	0.01	39	1220	42	10	6	19	0.02	< 10	< 10	37	< 10	246

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920341
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920341

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
23833	201 238	0.44	< 0.2	10	130	0.5	< 2	10.55	0.5	10	11	28	4.23	< 10	< 1	0.05	< 10	6.12	4110	< 1
23834	201 238	0.77	< 0.2	70	180	< 0.5	< 2	5.75	< 0.5	12	13	45	6.43	< 10	< 1	0.06	< 10	3.22	6690	< 1
23835	217 238	0.95	1.4	20	60	0.5	< 2	2.17	1.0	10	78	23	2.84	10	< 1	0.50	20	0.92	1645	< 1
23836	201 238	1.45	2.0	40	130	0.5	< 2	0.69	< 0.5	16	21	48	5.87	10	1	0.32	30	0.84	2590	< 1
23837	201 238	0.56	< 0.2	15	80	0.5	< 2	8.71	1.5	11	13	32	3.94	< 10	< 1	0.09	< 10	5.13	2840	< 1
23838	201 238	1.38	0.6	35	200	< 0.5	< 2	1.03	< 0.5	17	18	19	4.20	10	< 1	0.16	20	0.47	2450	< 1
23839	201 238	0.44	< 0.2	< 5	70	0.5	< 2	8.25	1.5	9	13	29	3.21	< 10	< 1	0.07	< 10	5.02	2460	< 1
23840	201 238	0.81	0.2	35	160	< 0.5	< 2	1.51	1.5	19	15	29	5.06	< 10	< 1	0.08	20	0.50	3660	< 1
23841	201 238	0.58	< 0.2	25	90	< 0.5	< 2	7.67	1.0	14	11	32	4.18	< 10	1	0.04	< 10	4.62	3200	< 1
23842	201 238	0.46	< 0.2	< 5	70	0.5	< 2	11.70	2.5	7	15	36	2.85	< 10	< 1	0.02	< 10	7.14	1800	< 1
23843	201 238	0.26	< 0.2	< 5	60	< 0.5	< 2	12.90	1.0	3	8	20	2.68	< 10	< 1	0.03	< 10	7.66	2470	< 1
23844	201 238	0.65	< 0.2	40	90	< 0.5	< 2	4.95	1.5	10	13	21	3.60	< 10	1	0.07	< 10	2.99	2250	< 1
23845	201 238	0.47	< 0.2	30	70	0.5	< 2	8.36	2.5	10	9	33	3.35	< 10	< 1	0.07	< 10	4.99	2600	< 1
23846	201 238	0.62	< 0.2	25	60	0.5	< 2	6.24	6.0	11	16	42	2.76	< 10	1	0.06	< 10	3.79	1660	< 1
23847	201 238	0.93	3.8	50	80	0.5	2	1.66	15.5	19	14	49	3.65	10	< 1	0.08	20	1.02	1595	< 1
23848	201 238	0.45	2.2	20	30	0.5	< 2	9.71	11.0	10	10	29	2.55	< 10	< 1	0.05	< 10	5.73	1620	< 1
23849	201 238	0.39	< 0.2	5	50	< 0.5	< 2	11.70	8.0	11	12	41	2.86	< 10	< 1	0.03	< 10	6.92	1935	< 1
23850	201 238	0.95	0.4	20	100	< 0.5	< 2	4.20	0.5	12	18	21	4.54	10	1	0.07	10	2.46	2210	< 1
23851	201 238	0.98	1.6	55	120	0.5	< 2	1.19	< 0.5	15	16	26	4.95	10	1	0.10	30	0.66	2210	< 1
23852	201 238	1.30	2.2	25	90	< 0.5	< 2	0.90	0.5	13	27	29	4.03	10	1	0.13	20	0.70	1195	< 1
23853	201 238	0.75	0.4	30	120	< 0.5	< 2	5.25	< 0.5	17	14	50	5.15	< 10	1	0.09	< 10	3.12	3790	< 1
23854	201 238	1.76	0.2	25	270	0.5	< 2	0.62	< 0.5	16	28	34	7.14	10	1	0.08	30	0.39	5200	3
23855	201 238	1.49	0.8	20	200	< 0.5	< 2	0.69	< 0.5	16	122	31	4.21	10	< 1	0.44	30	0.56	2840	2
23856	201 238	1.32	0.8	45	270	< 0.5	< 2	1.24	< 0.5	15	19	48	5.92	10	< 1	0.07	30	0.54	4720	5
23857	201 238	0.82	< 0.2	55	230	< 0.5	< 2	7.01	< 0.5	14	15	45	5.72	< 10	1	0.06	< 10	4.14	5730	1
23858	201 238	0.94	< 0.2	60	220	< 0.5	< 2	5.79	< 0.5	19	19	50	6.48	< 10	< 1	0.07	< 10	3.35	5540	1
23859	201 238	0.67	< 0.2	45	160	< 0.5	< 2	4.13	< 0.5	35	14	58	6.46	10	< 1	0.09	< 10	2.00	5090	2
23860	201 238	0.49	< 0.2	45	160	< 0.5	< 2	9.67	< 0.5	14	11	50	4.37	< 10	< 1	0.06	< 10	5.61	4010	< 1
23861	201 238	0.48	< 0.2	10	180	0.5	< 2	10.80	< 0.5	9	9	71	4.67	< 10	< 1	0.02	< 10	6.34	4440	< 1
23862	201 238	0.28	< 0.2	20	350	0.5	< 2	13.55	< 0.5	11	8	46	4.43	< 10	< 1	0.02	< 10	7.85	4760	6
23863	201 238	0.52	< 0.2	45	530	0.5	< 2	7.64	< 0.5	21	11	182	6.86	< 10	< 1	0.05	< 10	4.18	6990	8
23864	201 238	0.31	< 0.2	60	430	0.5	< 2	>15.00	< 0.5	< 1	13	114	7.49	< 10	2	0.03	< 10	>15.00	8770	4
23865	201 238	0.28	< 0.2	55	120	0.5	< 2	10.00	< 0.5	11	9	44	4.30	< 10	< 1	0.04	< 10	5.18	4000	6
23866	201 238	0.20	< 0.2	15	210	< 0.5	< 2	>15.00	< 0.5	5	7	20	3.87	< 10	< 1	0.02	< 10	8.99	3810	6
23867	201 238	0.50	< 0.2	70	1060	< 0.5	< 2	6.00	< 0.5	19	9	90	5.40	< 10	< 1	0.06	< 10	2.85	4170	8
23868	201 238	0.34	< 0.2	65	270	0.5	< 2	14.90	< 0.5	10	12	57	5.01	< 10	< 1	0.03	< 10	8.64	3740	10
23869	201 238	0.78	< 0.2	50	930	< 0.5	< 2	8.51	< 0.5	18	12	61	6.54	< 10	< 1	0.03	< 10	4.96	6750	7
23870	201 238	1.31	0.2	20	310	< 0.5	< 2	2.89	< 0.5	15	21	35	6.31	10	< 1	0.05	20	1.46	5270	2
23871	201 238	0.79	< 0.2	35	260	< 0.5	< 2	7.91	< 0.5	12	16	41	5.66	< 10	< 1	0.04	< 10	4.61	5160	< 1
23872	201 238	0.52	< 0.2	45	330	0.5	< 2	10.10	< 0.5	18	10	44	5.14	< 10	< 1	0.03	< 10	5.96	4860	11

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-B
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
23873	201 238	0.01	9	60	16	10	2	15	< 0.01	20	10	13	< 10	60
23874	201 238	0.01	24	410	36	10	4	25	< 0.01	20	< 10	17	< 10	220
23875	201 238	0.01	26	400	34	10	4	29	< 0.01	10	< 10	15	< 10	168
23876	201 238	0.01	26	730	58	10	4	20	0.01	10	< 10	22	< 10	190
23877	201 238	0.01	27	560	84	15	4	22	0.01	20	< 10	20	< 10	244
23878	201 238	0.01	35	1690	64	10	8	16	0.02	20	< 10	43	< 10	284
23879	201 238	0.01	42	1150	50	10	11	21	0.01	20	< 10	36	< 10	242
23880	201 238	< 0.01	48	1310	62	10	7	16	0.02	10	< 10	41	< 10	276
23881	201 238	0.01	29	660	36	10	4	20	0.01	20	< 10	25	< 10	166
23882	201 238	< 0.01	33	1150	48	5	6	10	0.02	20	< 10	42	< 10	174
23883	201 238	< 0.01	33	1270	56	< 5	5	12	0.02	20	< 10	40	< 10	228
23884	201 238	< 0.01	35	1090	60	5	5	11	0.02	10	< 10	39	< 10	272
23885	201 238	0.01	26	860	42	5	5	15	0.02	< 10	< 10	30	< 10	192
23886	201 238	0.01	19	680	274	10	5	27	0.01	< 10	< 10	18	< 10	442
23887	201 238	0.01	23	930	464	10	7	13	0.03	< 10	< 10	34	< 10	1485
23888	201 238	0.01	20	1120	404	5	4	17	0.03	< 10	< 10	28	< 10	1205
23889	201 238	0.01	28	720	3140	5	5	16	0.06	10	< 10	45	< 10	4780
23890	201 238	0.01	22	780	248	5	6	14	0.05	< 10	< 10	43	< 10	956
23891	201 238	0.01	17	430	972	5	5	17	0.01	< 10	< 10	15	< 10	3730
23892	201 238	0.01	17	410	3480	5	5	22	0.01	< 10	< 10	17	< 10	9920
23893	201 238	< 0.01	26	830	2050	10	5	12	0.02	< 10	< 10	28	< 10	6600
23894	201 238	< 0.01	23	740	704	10	5	20	0.01	< 10	< 10	25	< 10	3220
23895	201 238	0.01	24	350	1515	10	5	36	0.01	< 10	< 10	14	< 10	4280
23896	201 238	0.01	19	290	1485	10	4	35	0.01	< 10	< 10	12	< 10	5610
23897	201 238	0.01	25	580	2950	10	5	19	0.02	< 10	< 10	22	10	>10000
23898	201 238	0.01	24	550	3680	5	5	19	0.02	< 10	< 10	22	10	8740
23899	201 238	0.01	24	890	982	10	5	15	0.02	< 10	< 10	28	< 10	2850
24001	201 238	0.01	28	940	62	10	7	13	0.03	< 10	< 10	30	< 10	412
24002	201 238	0.01	25	1060	46	10	6	14	0.02	< 10	< 10	23	< 10	362
24003	201 238	0.01	27	1060	74	5	7	16	0.04	< 10	< 10	30	< 10	358
24004	201 238	0.01	23	980	56	10	7	16	0.04	< 10	< 10	37	< 10	384
24005	201 238	< 0.01	23	1030	58	5	5	12	0.02	< 10	< 10	24	< 10	442

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To : ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-A
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24014	201 238	1.47	0.2	30	180	< 0.5	< 2	2.33	1.0	22	20	66	4.96	10	< 1	0.25	20	2.13	2430	< 1
24015	201 238	0.43	< 0.2	105	60	< 0.5	< 2	6.18	0.5	19	6	26	6.14	< 10	< 1	0.03	< 10	3.76	2150	< 1
24016	201 238	0.43	0.2	170	60	< 0.5	< 2	4.57	< 0.5	23	8	28	6.88	< 10	< 1	0.04	< 10	2.74	2520	< 1
24017	201 238	0.58	< 0.2	80	90	< 0.5	< 2	7.08	< 0.5	14	5	30	4.55	< 10	1	0.04	< 10	4.38	2600	< 1
24018	201 238	0.68	< 0.2	65	120	< 0.5	< 2	5.26	< 0.5	17	11	31	4.96	< 10	< 1	0.05	< 10	3.24	2860	< 1
24019	201 238	0.53	< 0.2	65	90	< 0.5	< 2	7.23	0.5	16	9	28	4.84	< 10	< 1	0.04	< 10	4.38	2900	1
24020	201 238	0.45	< 0.2	60	70	< 0.5	< 2	9.36	0.5	10	7	20	4.11	< 10	< 1	0.03	< 10	5.71	3170	< 1
24021	201 238	0.58	< 0.2	105	90	< 0.5	< 2	6.31	< 0.5	19	11	29	5.11	< 10	< 1	0.04	< 10	3.80	2960	1
24022	201 238	0.36	< 0.2	65	60	0.5	< 2	9.84	0.5	13	7	22	4.80	< 10	< 1	0.02	< 10	5.68	3640	< 1
24023	201 238	0.44	< 0.2	65	70	< 0.5	< 2	7.71	0.5	13	10	21	5.04	< 10	< 1	0.02	< 10	4.53	4560	1
24024	201 238	0.42	< 0.2	50	70	0.5	< 2	9.12	0.5	14	8	23	4.22	< 10	1	0.02	< 10	5.26	2960	< 1
24025	201 238	0.52	< 0.2	65	90	< 0.5	< 2	7.87	< 0.5	14	11	16	4.44	< 10	< 1	0.04	< 10	4.50	3830	< 1
24026	201 238	0.84	1.0	125	110	0.5	2	2.66	0.5	24	15	25	7.04	10	< 1	0.07	10	1.72	3550	< 1
24027	201 238	1.39	< 0.2	100	180	< 0.5	< 2	5.09	< 0.5	27	18	33	6.55	< 10	< 1	0.11	< 10	3.76	4350	< 1
24028	201 238	1.17	< 0.2	55	270	< 0.5	< 2	3.69	0.5	23	18	28	6.97	10	1	0.11	10	2.28	6640	< 1
24029	201 238	0.61	< 0.2	80	90	0.5	< 2	8.11	< 0.5	22	12	22	5.09	< 10	< 1	0.06	< 10	4.85	3510	1
24030	201 238	0.72	< 0.2	55	250	< 0.5	< 2	7.10	0.5	22	12	33	4.67	< 10	< 1	0.08	< 10	4.23	3290	1
24031	201 238	0.95	< 0.2	75	540	< 0.5	< 2	3.75	< 0.5	22	17	29	5.65	10	< 1	0.11	< 10	2.36	3710	< 1
24032	201 238	0.77	< 0.2	175	250	< 0.5	< 2	5.30	< 0.5	28	10	34	6.50	< 10	< 1	0.10	< 10	3.28	3540	1
24033	201 238	1.21	0.4	85	450	< 0.5	< 2	0.89	< 0.5	16	17	31	5.81	10	< 1	0.11	20	0.68	3230	< 1
24034	201 238	0.68	0.2	155	210	< 0.5	< 2	4.11	< 0.5	22	6	28	5.88	< 10	< 1	0.04	< 10	2.47	3120	< 1
24035	201 238	0.58	< 0.2	95	140	0.5	< 2	6.55	< 0.5	14	9	22	4.58	< 10	< 1	0.04	< 10	3.85	3050	< 1
24036	201 238	0.96	< 0.2	75	220	0.5	6	3.63	< 0.5	17	17	32	4.63	< 10	1	0.07	< 10	2.26	2810	< 1
24037	201 238	0.95	0.2	65	230	< 0.5	4	2.23	< 0.5	17	17	50	4.19	10	< 1	0.10	10	1.38	1960	1
24038	201 238	0.86	0.2	60	140	0.5	< 2	3.33	< 0.5	17	15	46	3.64	< 10	1	0.09	< 10	2.10	1635	1
24039	201 238	0.96	0.2	80	310	< 0.5	< 2	2.42	< 0.5	18	15	54	4.39	< 10	1	0.09	10	1.41	2120	< 1
24040	201 238	1.01	< 0.2	70	150	0.5	< 2	1.08	< 0.5	17	13	50	4.50	< 10	1	0.09	20	0.72	2240	1
24041	201 238	0.94	< 0.2	65	140	0.5	2	2.25	< 0.5	19	14	48	4.00	10	1	0.11	10	1.57	2150	< 1
24042	201 238	1.04	0.4	90	140	< 0.5	4	1.42	< 0.5	17	15	47	4.20	10	< 1	0.12	20	1.03	2010	< 1
24043	201 238	1.72	0.4	75	120	0.5	2	1.06	< 0.5	16	18	43	3.93	10	< 1	0.34	20	1.57	1415	< 1
24044	201 238	1.64	0.2	50	90	0.5	4	0.81	< 0.5	12	17	28	2.73	< 10	< 1	0.60	20	1.47	725	1
24045	201 238	1.54	0.4	55	90	0.5	2	0.98	< 0.5	12	14	28	2.66	10	< 1	0.55	20	1.55	735	< 1
24046	201 238	1.45	0.4	85	130	< 0.5	< 2	0.61	< 0.5	16	17	42	4.17	10	< 1	0.17	20	0.77	1165	< 1
24047	201 238	0.78	< 0.2	80	60	0.5	< 2	4.52	< 0.5	15	10	34	3.44	< 10	< 1	0.12	< 10	2.86	1550	< 1
24048	201 238	1.25	0.4	90	130	< 0.5	< 2	0.78	< 0.5	16	13	47	4.93	10	< 1	0.17	20	0.80	2390	< 1
24049	201 238	1.33	0.2	60	150	0.5	4	0.94	< 0.5	16	19	41	4.55	10	< 1	0.10	20	0.63	2250	< 1
24050	201 238	1.20	0.4	65	130	1.5	4	0.65	< 0.5	16	19	53	4.49	10	2	0.13	20	0.55	1770	< 1
24051	201 238	1.19	0.2	55	130	1.0	2	1.09	< 0.5	13	56	47	4.21	10	< 1	0.23	20	0.59	1750	< 1
24052	201 238	1.22	< 0.2	75	120	0.5	4	1.03	< 0.5	11	16	23	4.43	10	< 1	0.08	20	0.58	1655	< 1
24053	201 238	0.97	0.2	65	120	< 0.5	2	1.11	< 0.5	15	14	24	3.71	< 10	1	0.10	20	0.80	1885	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 2-B
Total Pages: 5
Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24014	201 238	0.01	34	810	96	10	7	15	0.03	< 10	< 10	31	< 10	684
24015	201 238	0.01	61	450	60	20	4	12	0.01	< 10	< 10	14	10	218
24016	201 238	< 0.01	74	520	80	20	5	9	0.01	10	< 10	13	< 10	252
24017	201 238	0.01	36	480	34	10	5	15	0.01	< 10	< 10	17	< 10	438
24018	201 238	0.01	37	600	42	15	5	12	0.01	< 10	< 10	20	< 10	478
24019	201 238	0.01	36	490	36	10	4	15	0.01	10	< 10	19	< 10	520
24020	201 238	0.01	28	390	30	10	4	15	0.01	< 10	< 10	16	< 10	526
24021	201 238	0.01	41	500	68	10	5	14	0.01	10	< 10	17	< 10	698
24022	201 238	0.01	30	410	40	15	5	20	< 0.01	< 10	< 10	15	< 10	906
24023	201 238	0.01	29	460	30	15	5	17	< 0.01	10	< 10	15	10	778
24024	201 238	0.01	33	390	28	5	5	16	0.01	< 10	< 10	15	< 10	798
24025	201 238	0.01	28	490	24	10	6	14	0.01	< 10	< 10	15	< 10	296
24026	201 238	0.01	65	770	74	15	6	10	0.01	10	< 10	19	10	724
24027	201 238	0.01	51	720	48	15	9	15	0.02	10	< 10	29	10	298
24028	201 238	0.01	39	910	40	10	7	14	0.02	< 10	< 10	29	10	580
24029	201 238	0.01	43	510	46	10	5	16	0.01	< 10	< 10	16	10	326
24030	201 238	0.01	43	450	44	10	6	19	0.02	< 10	< 10	21	10	426
24031	201 238	0.01	31	630	38	10	6	10	0.02	10	< 10	27	< 10	280
24032	201 238	0.01	60	610	60	20	6	14	0.01	10	< 10	21	< 10	692
24033	201 238	< 0.01	28	900	42	10	6	9	0.02	< 10	< 10	33	< 10	512
24034	201 238	0.01	54	620	48	20	5	9	0.01	< 10	< 10	20	< 10	484
24035	201 238	0.01	33	590	36	15	4	12	0.01	< 10	< 10	18	< 10	434
24036	201 238	0.01	33	680	48	10	5	10	0.01	< 10	< 10	25	< 10	478
24037	201 238	0.01	27	840	88	10	6	15	0.02	< 10	< 10	27	< 10	550
24038	201 238	0.01	28	790	66	10	5	21	0.03	< 10	< 10	26	< 10	488
24039	201 238	0.01	28	900	96	15	6	15	0.02	< 10	< 10	25	< 10	552
24040	201 238	< 0.01	28	880	108	10	6	11	0.02	< 10	< 10	27	< 10	924
24041	201 238	0.01	30	700	116	10	6	13	0.02	< 10	< 10	26	< 10	660
24042	201 238	0.01	32	780	82	10	6	13	0.03	< 10	< 10	29	< 10	698
24043	201 238	0.01	35	900	124	10	6	11	0.03	< 10	< 10	28	< 10	960
24044	201 238	< 0.01	28	580	94	10	5	7	0.03	< 10	< 10	26	< 10	272
24045	201 238	< 0.01	28	550	88	10	5	7	0.03	< 10	< 10	23	< 10	246
24046	201 238	< 0.01	28	790	94	15	7	10	0.03	< 10	< 10	33	< 10	1625
24047	201 238	0.01	24	770	46	15	6	19	0.02	< 10	< 10	19	< 10	604
24048	201 238	< 0.01	30	870	58	15	6	10	0.03	< 10	< 10	29	< 10	802
24049	201 238	0.01	29	980	58	10	6	13	0.03	< 10	< 10	34	< 10	554
24050	201 238	0.01	28	910	92	10	7	12	0.03	< 10	< 10	32	< 10	736
24051	201 238	0.01	26	980	82	10	6	13	0.02	< 10	< 10	28	< 10	530
24052	201 238	< 0.01	21	1030	50	10	4	10	0.02	< 10	< 10	30	< 10	736
24053	201 238	< 0.01	27	590	168	10	6	21	0.03	< 10	< 10	29	< 10	532

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 3-A
Total Pages: 5
Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24054	201 238	0.90	< 0.2	40	240	< 0.5	< 2	2.27	< 0.5	18	15	33	3.71	< 10	3	0.07	10	1.41	2430	< 1
24055	201 238	1.13	0.4	75	280	< 0.5	< 2	0.74	< 0.5	17	20	32	6.56	10	4	0.05	20	0.54	5190	1
24056	201 238	1.15	< 0.2	65	180	< 0.5	< 2	2.78	< 0.5	12	18	27	3.94	< 10	1	0.03	10	1.76	2210	< 1
24057	201 238	1.30	< 0.2	45	190	< 0.5	< 2	3.22	< 0.5	12	19	26	3.96	< 10	< 1	0.07	10	2.01	2260	1
24058	201 238	1.48	0.2	110	270	< 0.5	< 2	1.13	< 0.5	16	19	27	7.06	10	3	0.09	20	0.56	6070	1
24059	201 238	1.50	0.2	50	250	< 0.5	< 2	0.71	< 0.5	17	21	28	7.11	10	< 1	0.06	30	0.50	5760	2
24060	201 238	1.45	0.4	70	220	< 0.5	2	0.83	< 0.5	17	22	29	6.11	10	1	0.09	30	0.62	4720	1
24061	201 238	1.30	0.6	70	220	< 0.5	< 2	1.96	< 0.5	17	18	42	6.07	10	4	0.08	20	1.30	4410	1
24062	201 238	1.25	0.4	45	220	< 0.5	2	1.72	< 0.5	14	23	34	7.09	10	2	0.07	20	0.91	5140	2
24063	201 238	1.55	0.4	80	190	< 0.5	< 2	0.73	< 0.5	16	19	35	6.26	10	5	0.12	20	0.79	3690	2
24064	201 238	0.97	< 0.2	55	130	< 0.5	< 2	5.00	< 0.5	15	14	42	4.72	< 10	2	0.08	< 10	2.92	3160	1
24065	201 238	0.79	0.2	30	140	< 0.5	< 2	3.09	< 0.5	15	16	23	6.16	10	1	0.05	< 10	1.56	5010	< 1
24066	201 238	0.80	< 0.2	45	180	< 0.5	< 2	3.19	< 0.5	16	9	44	5.20	< 10	< 1	0.07	< 10	1.60	4320	1
24067	201 238	1.06	0.4	70	250	< 0.5	< 2	2.65	< 0.5	17	16	31	6.07	10	1	0.07	10	1.20	4510	1
24068	201 238	0.63	< 0.2	95	130	< 0.5	< 2	7.71	< 0.5	22	11	29	4.18	< 10	5	0.06	< 10	3.88	3360	1
24069	201 238	0.76	< 0.2	65	140	< 0.5	< 2	5.49	< 0.5	18	11	39	4.24	< 10	< 1	0.09	< 10	3.07	2920	< 1
24070	201 238	0.64	< 0.2	75	130	< 0.5	< 2	7.83	< 0.5	11	13	29	3.60	< 10	1	0.05	< 10	4.43	2840	1
24071	201 238	0.77	< 0.2	70	120	< 0.5	< 2	6.36	2.0	14	15	34	4.25	< 10	4	0.07	< 10	3.68	3250	1
24072	201 238	0.49	< 0.2	60	50	< 0.5	2	4.61	0.5	15	6	24	3.70	< 10	< 1	0.05	< 10	2.47	1835	< 1
24073	201 238	1.26	2.0	45	100	< 0.5	< 2	1.49	< 0.5	22	26	82	5.42	10	< 1	0.10	20	1.12	2310	< 1
24074	201 238	1.59	2.8	60	60	< 0.5	< 2	1.73	< 0.5	25	26	129	6.67	10	< 1	0.11	20	1.68	1485	< 1
24075	201 238	0.53	5.6	40	40	< 0.5	< 2	7.41	3.0	16	9	53	3.48	< 10	2	0.07	< 10	4.62	2120	< 1
24076	201 238	0.69	2.4	65	70	< 0.5	< 2	4.98	< 0.5	20	10	61	4.19	< 10	4	0.06	< 10	3.04	2130	1
24077	201 238	0.91	1.2	55	120	< 0.5	< 2	4.53	0.5	13	13	46	4.28	< 10	4	0.06	< 10	3.00	2930	< 1
24078	201 238	0.58	< 0.2	40	60	< 0.5	< 2	8.03	1.0	13	10	53	3.26	< 10	< 1	0.07	< 10	5.17	1875	< 1
24079	201 238	0.63	< 0.2	40	90	< 0.5	< 2	8.54	3.0	10	8	50	4.08	< 10	4	0.07	< 10	5.63	2970	1
24080	201 238	0.61	< 0.2	25	70	< 0.5	< 2	8.42	3.0	9	13	47	3.80	< 10	2	0.06	< 10	5.54	2550	1
24081	201 238	0.99	3.2	80	120	< 0.5	< 2	3.34	6.5	17	14	61	5.39	< 10	5	0.08	10	2.16	3010	2
24082	201 238	0.80	1.4	45	70	< 0.5	< 2	6.08	5.0	11	11	37	3.76	< 10	3	0.07	< 10	3.95	2690	1
24083	201 238	0.57	< 0.2	35	50	< 0.5	< 2	8.77	3.0	8	11	23	2.49	< 10	4	0.06	< 10	5.61	1425	1
24084	201 238	0.72	0.4	15	60	< 0.5	< 2	6.01	3.5	11	12	20	3.24	< 10	< 1	0.07	< 10	3.68	2090	< 1
24085	201 238	0.99	1.6	25	60	0.5	2	3.02	2.0	9	16	26	3.82	10	7	0.06	10	1.88	1175	1
24086	201 238	0.66	0.6	25	80	< 0.5	2	4.01	1.5	14	14	30	3.81	10	3	0.07	< 10	2.41	2220	< 1
24087	201 238	0.73	1.0	50	80	< 0.5	< 2	2.17	0.5	15	13	29	4.52	10	5	0.07	20	1.22	2440	< 1
24088	201 238	0.64	< 0.2	25	100	< 0.5	< 2	4.85	1.0	13	14	26	4.11	< 10	5	0.06	< 10	2.93	2840	1
24089	201 238	1.02	0.8	25	160	< 0.5	2	2.90	< 0.5	15	18	47	4.38	10	3	0.11	10	1.80	2470	3
24090	201 238	1.06	< 0.2	30	140	< 0.5	< 2	4.38	0.5	16	22	35	4.24	< 10	4	0.09	< 10	2.96	2820	1
24091	201 238	0.84	< 0.2	25	100	< 0.5	< 2	4.48	0.5	17	19	29	4.11	10	1	0.08	< 10	2.77	2840	< 1
24092	201 238	1.26	1.0	20	190	< 0.5	< 2	0.85	0.5	14	22	21	6.02	10	4	0.06	30	0.57	4410	1
24093	201 238	1.28	1.2	5	110	< 0.5	< 2	0.56	< 0.5	14	21	29	5.00	10	3	0.05	30	0.53	2940	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24054	201	238	0.01	31	830	90	10	5	19	0.02	< 10	< 10	27	< 10	284
24055	201	238	< 0.01	36	680	302	10	8	12	0.03	10	< 10	38	< 10	524
24056	201	238	0.01	27	730	136	10	5	16	0.04	< 10	< 10	36	< 10	274
24057	201	238	0.01	25	750	130	10	6	21	0.05	< 10	< 10	42	< 10	272
24058	201	238	0.01	27	1140	242	15	7	15	0.03	< 10	< 10	45	< 10	574
24059	201	238	< 0.01	30	960	136	15	7	12	0.04	< 10	< 10	44	< 10	388
24060	201	238	< 0.01	31	820	108	10	7	13	0.04	< 10	< 10	42	< 10	342
24061	201	238	0.01	31	850	228	15	7	16	0.03	< 10	< 10	42	< 10	496
24062	201	238	< 0.01	30	1100	206	10	6	13	0.02	10	< 10	40	< 10	746
24063	201	238	0.01	30	900	138	10	7	13	0.03	< 10	< 10	42	< 10	436
24064	201	238	0.01	29	960	250	15	5	19	0.02	< 10	< 10	30	< 10	416
24065	201	238	< 0.01	22	820	340	10	5	13	0.01	10	< 10	25	< 10	454
24066	201	238	0.01	26	990	204	10	4	14	0.01	< 10	< 10	26	< 10	472
24067	201	238	0.01	36	1110	228	15	5	16	0.02	< 10	< 10	32	< 10	648
24068	201	238	0.01	33	620	98	15	5	37	0.01	< 10	< 10	24	< 10	210
24069	201	238	0.01	31	800	114	10	6	28	0.02	< 10	< 10	24	< 10	272
24070	201	238	0.01	24	630	204	15	4	33	0.02	< 10	< 10	23	< 10	524
24071	201	238	0.01	26	690	362	15	6	27	0.02	< 10	< 10	25	< 10	1450
24072	201	238	0.01	21	690	472	15	5	36	0.01	< 10	< 10	17	< 10	1455
24073	201	238	0.01	35	860	410	15	11	28	0.02	< 10	< 10	44	< 10	694
24074	201	238	0.01	36	730	790	15	13	27	0.02	10	< 10	43	< 10	900
24075	201	238	0.01	22	510	3510	15	5	35	0.01	10	< 10	16	< 10	2840
24076	201	238	0.01	28	790	784	15	7	27	0.01	10	< 10	20	< 10	1070
24077	201	238	0.01	26	500	526	10	5	17	0.02	10	< 10	28	< 10	1040
24078	201	238	0.01	23	500	634	10	4	25	0.01	20	< 10	19	< 10	1325
24079	201	238	0.01	21	510	776	10	5	24	0.01	20	< 10	22	< 10	2300
24080	201	238	0.01	22	530	688	10	5	24	0.02	10	< 10	21	< 10	2120
24081	201	238	0.01	32	880	1850	15	6	18	0.02	10	< 10	30	< 10	5920
24082	201	238	0.01	23	610	1760	15	4	17	0.01	10	< 10	23	< 10	3450
24083	201	238	0.01	18	410	604	10	4	40	0.02	10	< 10	18	< 10	2440
24084	201	238	0.01	19	530	1175	5	5	26	0.02	10	< 10	22	< 10	2270
24085	201	238	0.01	19	780	752	10	5	17	0.02	< 10	< 10	29	< 10	2190
24086	201	238	0.01	21	670	590	10	5	38	0.01	< 10	< 10	23	< 10	1335
24087	201	238	< 0.01	22	780	374	10	6	29	0.01	< 10	< 10	23	< 10	1080
24088	201	238	0.01	22	600	284	10	6	42	0.02	< 10	< 10	23	< 10	820
24089	201	238	0.01	30	760	208	10	5	17	0.01	< 10	< 10	30	< 10	362
24090	201	238	0.01	29	500	224	10	6	16	0.02	10	< 10	32	< 10	600
24091	201	238	0.01	29	570	474	10	5	20	0.02	10	< 10	27	< 10	556
24092	201	238	< 0.01	24	620	218	5	6	12	0.03	10	< 10	35	< 10	446
24093	201	238	< 0.01	27	600	196	5	6	9	0.02	< 10	< 10	34	< 10	378

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 1S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24094	201	238	1.55	1.2	15	230	0.5	< 2	1.12	0.5	15	22	24	5.06	10	1	0.07	20	0.73	3170	< 1
24095	201	238	1.48	1.2	20	210	< 0.5	< 2	0.98	< 0.5	15	22	24	4.87	10	< 1	0.07	20	0.70	3030	< 1
24096	201	238	1.45	1.0	5	220	< 0.5	< 2	1.08	1.0	15	21	31	5.74	10	< 1	0.08	20	0.58	4230	1
24097	201	238	1.83	0.8	55	200	< 0.5	< 2	0.58	< 0.5	14	25	18	6.76	10	2	0.06	30	0.56	4120	1
24098	201	238	1.88	0.8	25	160	< 0.5	2	0.52	< 0.5	10	29	13	5.30	10	1	0.06	20	0.54	2130	1
24099	201	238	2.06	0.8	20	170	< 0.5	< 2	0.51	< 0.5	11	30	15	5.39	10	< 1	0.08	20	0.58	1925	1
24100	201	238	1.73	0.8	25	160	< 0.5	< 2	0.16	< 0.5	13	21	11	4.98	10	< 1	0.08	20	0.35	2100	1
24101	201	238	1.63	0.8	55	190	< 0.5	< 2	0.57	< 0.5	14	20	12	5.60	10	3	0.08	20	0.54	3230	2
24102	201	238	1.84	0.6	5	210	< 0.5	2	0.41	< 0.5	8	21	8	4.75	10	< 1	0.07	20	0.44	1805	1
24103	201	238	1.45	0.6	5	70	0.5	2	1.66	< 0.5	13	28	50	4.35	10	< 1	0.09	20	1.52	1365	< 1
24104	201	238	1.03	0.2	35	90	< 0.5	< 2	2.73	< 0.5	21	19	50	4.03	< 10	< 1	0.12	10	1.83	2300	< 1
24105	201	238	1.60	0.8	25	140	< 0.5	< 2	0.66	< 0.5	20	33	63	5.39	10	< 1	0.12	20	1.00	2940	< 1
24106	201	238	1.03	< 0.2	10	110	< 0.5	< 2	5.10	0.5	14	17	34	4.39	< 10	1	0.13	< 10	3.41	2980	< 1
24107	201	238	1.71	0.6	20	230	< 0.5	< 2	0.35	< 0.5	13	23	29	5.59	10	1	0.08	20	0.55	2450	1
24108	201	238	1.88	0.6	10	210	0.5	< 2	0.47	< 0.5	13	24	34	5.12	10	2	0.08	30	0.71	1825	1
24109	201	238	1.75	0.8	25	190	< 0.5	< 2	0.38	< 0.5	13	24	32	5.00	10	< 1	0.09	30	0.65	1790	< 1
24110	201	238	1.92	0.8	5	190	< 0.5	< 2	0.35	< 0.5	14	27	32	5.33	10	< 1	0.08	20	0.66	1810	1
24111	201	238	1.58	0.4	< 5	160	< 0.5	< 2	0.31	< 0.5	13	23	19	4.81	10	< 1	0.08	20	0.60	1655	< 1
24112	201	238	1.21	1.0	10	390	< 0.5	< 2	1.19	< 0.5	10	20	31	4.68	10	< 1	0.07	20	0.67	1905	1
24113	201	238	1.37	1.0	40	410	< 0.5	< 2	1.45	< 0.5	11	23	34	4.54	10	< 1	0.07	20	0.69	1855	1
24114	201	238	1.53	1.0	45	390	< 0.5	< 2	1.10	< 0.5	11	21	30	4.92	10	2	0.12	30	0.75	1980	1
24115	201	238	1.62	1.0	< 5	140	< 0.5	< 2	0.83	< 0.5	11	23	34	4.87	10	< 1	0.11	30	0.70	1220	1
24116	201	238	1.56	0.8	15	130	< 0.5	< 2	0.74	< 0.5	8	22	32	4.60	10	< 1	0.10	20	0.69	805	1
24117	201	238	1.06	0.8	< 5	160	< 0.5	< 2	0.77	< 0.5	10	16	29	3.96	10	< 1	0.10	20	0.60	1370	1
24118	201	238	1.38	2.4	5	130	< 0.5	< 2	1.55	3.0	13	21	22	5.49	10	1	0.07	20	1.04	3020	< 1
24119	201	238	1.29	0.8	15	190	< 0.5	< 2	0.67	< 0.5	13	23	15	6.34	10	< 1	0.08	30	0.63	5370	< 1
24120	201	238	0.87	< 0.2	15	110	< 0.5	< 2	4.79	< 0.5	14	15	39	3.98	< 10	1	0.09	< 10	3.18	2260	< 1
24121	201	238	1.15	1.0	30	200	< 0.5	< 2	1.48	0.5	16	19	40	5.05	10	< 1	0.09	20	1.06	2750	1
24122	201	238	0.96	1.8	30	130	< 0.5	< 2	1.20	2.5	15	14	38	5.00	10	< 1	0.08	20	0.64	2740	1
24123	201	238	0.78	2.2	45	110	< 0.5	2	2.13	2.5	16	12	44	4.75	10	< 1	0.07	10	1.03	3220	< 1
24124	201	238	0.64	1.0	< 5	100	< 0.5	< 2	4.05	3.5	15	12	37	3.97	< 10	< 1	0.07	< 10	2.17	2970	< 1
24125	201	238	0.53	< 0.2	< 5	70	< 0.5	< 2	6.23	1.5	10	9	34	3.60	< 10	< 1	0.05	< 10	3.73	2130	< 1
24126	201	238	0.61	< 0.2	5	90	< 0.5	< 2	5.73	2.5	11	10	37	3.96	< 10	< 1	0.07	< 10	3.46	2600	< 1
24127	201	238	1.66	1.0	40	180	< 0.5	< 2	0.60	2.5	12	25	15	5.12	10	< 1	0.08	20	0.50	2410	1
24128	201	238	1.62	0.8	30	170	< 0.5	< 2	0.76	17.0	11	25	18	4.36	10	< 1	0.08	20	0.56	1755	< 1
24129	201	238	1.71	0.8	10	120	< 0.5	< 2	0.83	2.0	9	27	14	4.07	10	< 1	0.07	10	0.58	1265	< 1
24130	201	238	1.71	0.6	30	180	< 0.5	< 2	0.55	< 0.5	9	27	13	3.66	10	< 1	0.08	20	0.56	870	1
24131	201	238	0.73	< 0.2	50	40	< 0.5	< 2	7.48	14.0	19	12	39	3.46	< 10	4	0.08	< 10	4.99	1440	1
24132	201	238	0.70	< 0.2	55	50	< 0.5	< 2	6.60	4.5	15	13	37	3.66	< 10	< 1	0.06	< 10	4.31	1515	< 1
24133	201	238	0.28	< 0.2	100	20	< 0.5	< 2	8.46	3.0	16	6	22	3.83	< 10	< 1	0.04	< 10	4.87	1700	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24094	201 238	0.01	23	970	208	5	6	15	0.03	< 10	< 10	39	< 10	456
24095	201 238	0.01	25	880	210	5	6	14	0.03	< 10	< 10	38	< 10	444
24096	201 238	0.01	26	900	196	5	6	14	0.03	< 10	< 10	42	< 10	558
24097	201 238	< 0.01	26	740	110	10	8	13	0.05	< 10	< 10	56	< 10	280
24098	201 238	0.01	22	720	72	5	6	12	0.04	< 10	< 10	52	< 10	202
24099	201 238	0.01	22	760	72	5	7	14	0.05	< 10	< 10	57	< 10	204
24100	201 238	< 0.01	22	520	80	10	5	7	0.04	< 10	< 10	46	< 10	152
24101	201 238	0.01	19	820	406	10	6	13	0.04	< 10	< 10	48	< 10	352
24102	201 238	< 0.01	14	580	128	5	6	11	0.04	< 10	< 10	48	< 10	278
24103	201 238	0.01	23	760	212	5	7	13	0.03	< 10	< 10	38	< 10	528
24104	201 238	0.01	27	940	68	5	6	29	0.02	< 10	< 10	27	< 10	232
24105	201 238	< 0.01	31	510	114	5	8	13	0.03	< 10	< 10	46	< 10	360
24106	201 238	0.01	27	650	148	10	7	20	0.02	< 10	< 10	24	< 10	338
24107	201 238	< 0.01	26	720	70	5	5	9	0.03	< 10	< 10	44	< 10	286
24108	201 238	< 0.01	28	530	62	5	7	9	0.02	< 10	< 10	47	< 10	178
24109	201 238	< 0.01	28	510	80	10	7	8	0.02	< 10	< 10	43	< 10	172
24110	201 238	< 0.01	28	530	58	10	7	8	0.02	< 10	< 10	46	< 10	198
24111	201 238	< 0.01	23	570	48	5	5	10	0.03	< 10	< 10	41	< 10	204
24112	201 238	< 0.01	23	940	78	5	6	12	0.02	< 10	< 10	31	< 10	206
24113	201 238	0.01	25	1160	66	5	5	15	0.02	< 10	< 10	32	< 10	170
24114	201 238	< 0.01	25	960	66	5	6	14	0.03	< 10	< 10	40	< 10	194
24115	201 238	0.01	24	860	66	5	7	14	0.03	< 10	< 10	43	< 10	274
24116	201 238	0.01	21	880	62	5	6	13	0.03	< 10	< 10	44	< 10	288
24117	201 238	< 0.01	21	660	54	5	4	9	0.01	< 10	< 10	31	< 10	292
24118	201 238	< 0.01	22	710	704	10	6	12	0.03	< 10	< 10	44	< 10	1430
24119	201 238	0.01	27	740	38	5	8	11	0.03	< 10	< 10	32	< 10	172
24120	201 238	0.01	29	690	60	5	5	21	0.02	< 10	< 10	24	< 10	144
24121	201 238	0.01	31	700	142	5	6	13	0.03	< 10	< 10	34	< 10	568
24122	201 238	< 0.01	25	870	680	5	5	22	0.02	< 10	< 10	27	< 10	1850
24123	201 238	0.01	25	990	974	10	5	14	0.01	< 10	< 10	23	< 10	2530
24124	201 238	0.01	23	900	828	5	4	17	0.01	< 10	< 10	19	< 10	2150
24125	201 238	0.01	18	690	548	10	4	20	0.01	< 10	< 10	17	< 10	1400
24126	201 238	0.01	19	660	562	5	4	19	0.01	< 10	< 10	19	< 10	1580
24127	201 238	< 0.01	20	720	188	5	6	12	0.04	< 10	< 10	48	< 10	1870
24128	201 238	< 0.01	19	680	68	< 5	5	14	0.04	< 10	< 10	47	< 10	7840
24129	201 238	< 0.01	16	920	118	5	4	14	0.04	< 10	< 10	49	< 10	2070
24130	201 238	0.01	18	420	156	< 5	5	16	0.07	< 10	< 10	56	< 10	608
24131	201 238	0.01	37	630	1560	10	5	70	< 0.01	< 10	< 10	15	< 10	9450
24132	201 238	0.01	28	560	650	5	5	39	0.01	< 10	< 10	17	< 10	4630
24133	201 238	< 0.01	34	370	100	10	4	51	< 0.01	< 10	< 10	9	< 10	3660

CERTIFICATION

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J 2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDP
Comments:

Date : 25-JUL-89
Invoice # I-8920343
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24134	201 238	0.72	1.4	65	60	< 0.5	4	4.87	7.5	20	12	31	3.94	< 10	< 1	0.06	< 10	3.08	1675	< 1
24135	201 238	0.82	1.4	75	40	< 0.5	4	3.53	4.0	14	13	31	4.18	< 10	< 1	0.06	< 10	2.19	895	< 1
24136	201 238	0.60	4.4	90	50	< 0.5	4	3.93	12.0	26	10	53	3.83	< 10	< 1	0.07	< 10	2.35	2140	< 1
24137	201 238	0.60	3.6	70	30	< 0.5	2	6.44	14.5	19	10	44	3.37	< 10	< 1	0.07	< 10	3.86	1360	< 1
24138	201 238	1.19	1.0	35	160	< 0.5	6	1.55	3.5	22	19	45	5.05	< 10	< 1	0.10	10	0.91	3500	< 1
24139	201 238	0.74	1.4	35	120	< 0.5	4	5.01	3.5	21	13	41	4.56	< 10	< 1	0.09	< 10	2.89	3480	< 1
24140	201 238	0.14	0.8	65	40	< 0.5	2	11.60	< 0.5	53	2	36	3.75	< 10	< 1	0.02	< 10	6.35	3080	< 1
24141	201 238	1.17	1.0	35	120	< 0.5	4	0.84	1.5	19	19	47	5.32	< 10	< 1	0.08	20	0.59	1975	< 1
24142	201 238	1.24	1.0	25	220	< 0.5	6	0.88	1.5	24	22	65	6.25	< 10	< 1	0.12	30	0.65	3820	< 1
24143	201 238	1.29	0.8	35	270	< 0.5	6	1.43	0.5	20	28	50	6.50	< 10	< 1	0.11	20	1.03	3660	1
24144	201 238	1.70	1.8	50	140	< 0.5	4	1.01	2.0	16	23	30	4.62	< 10	< 1	0.11	20	0.67	1235	1
24145	201 238	1.68	1.8	35	150	< 0.5	2	0.92	1.5	15	24	42	4.76	< 10	< 1	0.13	20	0.67	905	1
24146	201 238	1.40	0.6	20	170	< 0.5	2	0.56	1.0	16	25	23	3.89	< 10	3	0.08	20	0.62	1130	< 1
24147	201 238	1.29	0.8	25	260	< 0.5	2	1.07	1.0	16	19	16	4.05	< 10	< 1	0.07	10	0.52	2440	1
24148	201 238	1.41	0.4	20	310	< 0.5	2	0.40	< 0.5	14	22	27	4.66	< 10	< 1	0.08	20	0.53	1600	1
24149	201 238	1.77	0.2	10	200	< 0.5	< 2	0.14	0.5	8	29	14	4.36	< 10	< 1	0.08	20	0.42	605	1
24150	201 238	1.38	1.0	20	270	< 0.5	2	0.48	0.5	18	26	58	5.58	< 10	< 1	0.10	30	0.93	2750	1
24151	201 238	1.31	0.8	15	230	< 0.5	6	0.49	0.5	15	24	48	5.23	< 10	< 1	0.09	30	0.80	2420	1
24152	201 238	1.67	0.4	10	140	< 0.5	< 2	0.20	< 0.5	10	28	20	4.12	< 10	1	0.08	20	0.89	1110	1
24349	201 238	1.30	0.6	20	170	< 0.5	2	0.91	1.5	17	19	30	4.13	< 10	< 1	0.12	20	0.65	2300	1
24350	201 238	1.68	0.8	15	170	< 0.5	< 2	0.81	0.5	19	29	40	4.66	< 10	< 1	0.12	20	0.76	1995	1
24351	201 238	1.33	0.6	15	140	< 0.5	2	1.09	0.5	16	21	32	4.48	< 10	< 1	0.14	20	0.89	2460	1
24352	201 238	1.57	0.4	20	130	< 0.5	2	0.79	< 0.5	15	23	32	4.65	< 10	< 1	0.15	30	0.81	1705	< 1
24353	201 238	1.94	0.4	20	160	< 0.5	< 2	0.51	< 0.5	14	31	23	4.02	< 10	< 1	0.20	30	1.06	1230	1
24354	201 238	2.02	0.6	25	160	< 0.5	4	1.06	0.5	16	28	33	4.38	< 10	1	0.29	20	1.62	1835	< 1
24355	201 238	1.34	0.6	35	120	< 0.5	2	0.98	0.5	24	21	32	5.17	< 10	< 1	0.20	20	0.93	2390	3
24356	201 238	1.99	0.4	< 5	80	< 0.5	4	1.34	1.0	15	24	32	2.96	< 10	< 1	0.26	10	2.25	865	1
24357	201 238	1.98	0.4	20	70	< 0.5	< 2	2.92	< 0.5	18	25	39	2.84	< 10	2	0.30	< 10	3.01	670	< 1
24358	201 238	1.61	0.6	< 5	70	< 0.5	2	2.47	0.5	15	22	32	2.99	< 10	< 1	0.29	< 10	2.78	755	< 1
24359	201 238	1.21	0.6	10	90	< 0.5	< 2	3.09	< 0.5	16	22	36	2.74	< 10	3	0.19	< 10	2.47	780	< 1
24360	201 238	0.99	0.8	15	100	< 0.5	4	3.46	0.5	17	18	45	3.30	< 10	3	0.13	< 10	2.35	1175	1
24361	201 238	1.73	0.6	5	110	< 0.5	2	1.20	0.5	17	25	43	3.69	< 10	< 1	0.23	20	1.65	800	< 1
24362	201 238	1.08	0.6	10	90	< 0.5	2	3.96	0.5	17	21	32	3.48	< 10	< 1	0.10	< 10	2.63	1455	< 1
24363	201 238	1.39	0.6	20	150	< 0.5	2	1.74	< 0.5	20	24	59	5.14	< 10	< 1	0.12	10	1.45	3210	2
24364	201 238	1.15	0.4	25	180	< 0.5	2	0.73	1.0	15	22	24	5.64	< 10	1	0.06	20	0.42	3450	1
24365	201 238	1.30	0.8	40	220	< 0.5	< 2	0.75	0.5	17	19	38	3.71	< 10	< 1	0.13	20	0.64	1115	2
24366	201 238	1.00	1.4	125	240	< 0.5	2	1.70	1.0	30	16	42	6.29	< 10	< 1	0.13	10	1.02	1580	2
24367	201 238	1.97	0.6	15	170	< 0.5	< 2	0.69	1.0	18	31	18	5.93	< 10	< 1	0.11	20	1.15	3060	< 1
24368	201 238	1.11	1.2	85	290	< 0.5	4	1.62	1.0	32	20	73	7.13	< 10	< 1	0.12	10	1.25	3240	2
24369	201 238	0.75	1.2	80	180	< 0.5	4	5.80	5.0	27	14	72	4.73	< 10	< 1	0.09	< 10	3.63	2240	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920343
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920343

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24134	201 238	< 0.01	37	500	256	< 5	5	26	0.01	< 10	< 10	20	10	6230
24135	201 238	< 0.01	29	770	370	5	5	18	0.01	< 10	< 10	22	< 10	3890
24136	201 238	< 0.01	40	710	1950	5	4	21	< 0.01	< 10	< 10	17	10	>10000
24137	201 238	0.01	38	520	1495	5	4	24	0.01	< 10	< 10	17	10	>10000
24138	201 238	0.01	30	910	368	5	6	17	0.02	< 10	< 10	30	< 10	2800
24139	201 238	0.01	30	700	364	< 5	6	15	0.01	< 10	< 10	22	< 10	2640
24140	201 238	0.01	27	350	74	10	3	22	< 0.01	< 10	< 10	5	< 10	358
24141	201 238	< 0.01	22	840	424	5	6	10	0.02	< 10	< 10	31	< 10	1500
24142	201 238	< 0.01	38	960	186	< 5	7	11	0.02	< 10	< 10	36	< 10	1220
24143	201 238	< 0.01	36	910	202	< 5	8	13	0.03	< 10	< 10	41	< 10	778
24144	201 238	0.01	25	1300	766	5	5	15	0.03	< 10	< 10	38	< 10	1970
24145	201 238	0.01	25	1230	776	< 5	5	15	0.03	< 10	< 10	38	< 10	2040
24146	201 238	< 0.01	29	440	220	< 5	4	12	0.04	< 10	< 10	41	< 10	1450
24147	201 238	< 0.01	15	890	482	< 5	4	15	0.03	< 10	< 10	41	< 10	972
24148	201 238	< 0.01	22	620	104	5	5	16	0.03	< 10	< 10	41	< 10	450
24149	201 238	< 0.01	12	380	102	< 5	3	9	0.04	< 10	< 10	58	< 10	306
24150	201 238	< 0.01	40	660	70	< 5	10	10	0.03	< 10	< 10	40	< 10	226
24151	201 238	< 0.01	31	540	90	< 5	8	9	0.02	< 10	< 10	40	< 10	262
24152	201 238	< 0.01	16	550	86	< 5	3	9	0.03	< 10	< 10	53	< 10	300
24349	201 238	< 0.01	22	860	56	< 5	5	10	0.02	< 10	< 10	30	< 10	900
24350	201 238	0.01	28	800	64	< 5	7	13	0.03	< 10	< 10	41	< 10	704
24351	201 238	< 0.01	25	590	46	< 5	6	11	0.03	< 10	< 10	34	< 10	488
24352	201 238	< 0.01	23	580	40	5	7	12	0.03	< 10	< 10	38	< 10	342
24353	201 238	< 0.01	27	700	34	< 5	6	11	0.03	< 10	< 10	42	< 10	420
24354	201 238	0.01	28	750	44	5	7	14	0.04	< 10	< 10	41	< 10	386
24355	201 238	< 0.01	35	580	118	5	7	10	0.02	< 10	< 10	31	< 10	616
24356	201 238	< 0.01	24	710	88	< 5	5	15	0.02	< 10	< 10	29	< 10	398
24357	201 238	< 0.01	23	640	72	5	5	31	0.03	< 10	< 10	30	< 10	414
24358	201 238	0.01	24	640	56	< 5	5	17	0.03	< 10	< 10	26	< 10	452
24359	201 238	0.01	23	800	46	5	5	26	0.05	< 10	< 10	33	< 10	308
24360	201 238	0.01	24	690	50	5	5	21	0.03	< 10	< 10	28	< 10	430
24361	201 238	0.01	26	830	68	< 5	5	13	0.03	< 10	< 10	31	< 10	464
24362	201 238	0.01	25	770	22	5	5	21	0.04	< 10	< 10	32	< 10	258
24363	201 238	< 0.01	31	340	48	5	6	7	0.01	< 10	< 10	29	< 10	482
24364	201 238	< 0.01	23	980	40	< 5	5	7	0.01	< 10	< 10	28	< 10	548
24365	201 238	< 0.01	27	630	70	5	5	8	0.01	< 10	< 10	26	< 10	832
24366	201 238	< 0.01	56	670	94	10	5	11	0.01	< 10	< 10	24	< 10	810
24367	201 238	< 0.01	35	810	78	< 5	11	9	0.03	< 10	< 10	46	< 10	638
24368	201 238	< 0.01	56	610	78	10	8	9	0.02	< 10	< 10	34	< 10	846
24369	201 238	0.01	40	480	140	5	5	16	0.02	< 10	< 10	22	< 10	3430

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-A
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24370	201 238	0.76	0.8	60	130	1.5	4	2.86	3.0	20	13	26	4.79	< 10	< 1	0.05	< 10	1.74	2680	1
24371	201 238	0.38	2.0	220	150	0.5	4	7.96	7.0	40	8	54	5.73	< 10	< 1	0.04	< 10	4.76	1820	2
24372	201 238	0.42	2.6	225	130	0.5	< 2	6.04	9.0	33	8	54	6.23	< 10	< 1	0.04	< 10	3.64	1430	2
24373	201 238	0.22	1.4	60	50	0.5	< 2	9.77	11.5	21	5	43	3.25	< 10	< 1	0.03	< 10	5.67	1790	< 1
24374	201 238	0.16	3.2	125	20	0.5	2	7.50	9.0	27	4	41	4.38	< 10	< 1	0.04	< 10	4.35	885	1
24375	201 238	0.21	2.8	285	50	< 0.5	4	9.55	11.0	35	4	43	6.26	< 10	< 1	0.03	< 10	5.63	1340	2
24376	201 238	0.25	1.8	60	60	0.5	< 2	9.55	13.5	20	5	67	3.34	< 10	< 1	0.04	< 10	5.52	1625	1
24377	201 238	0.21	2.2	120	50	< 0.5	4	8.76	14.0	30	5	52	4.28	< 10	< 1	0.04	< 10	5.14	1490	1
24378	201 238	0.58	3.4	245	80	0.5	4	3.64	13.0	24	10	56	7.26	< 10	< 1	0.08	< 10	2.18	965	2
24379	201 238	0.56	1.6	130	120	0.5	2	7.09	6.5	25	10	47	4.74	< 10	< 1	0.07	< 10	4.32	1860	1
24380	201 238	1.17	2.4	150	240	0.5	4	2.87	8.5	33	18	77	7.01	< 10	< 1	0.13	< 10	2.17	2850	3
24381	201 238	1.25	0.8	40	240	0.5	< 2	0.96	2.0	18	23	27	6.25	< 10	< 1	0.06	20	0.52	3960	1
24382	201 238	1.65	0.6	25	170	1.0	2	0.61	1.0	20	28	27	4.49	< 10	< 1	0.13	20	0.79	1980	1
24383	201 238	1.75	0.4	25	190	0.5	2	0.46	0.5	19	28	23	4.28	< 10	< 1	0.12	20	0.64	1950	2
24384	201 238	1.59	1.0	45	190	0.5	2	0.55	1.5	24	28	34	5.55	< 10	< 1	0.11	30	0.88	2140	2
24385	201 238	1.34	1.0	35	180	0.5	< 2	2.46	1.5	21	23	48	4.31	< 10	< 1	0.11	< 10	1.70	1785	< 1
24386	201 238	1.81	0.6	15	190	< 0.5	2	0.77	1.5	16	28	40	3.78	< 10	< 1	0.14	20	0.75	985	1
24387	201 238	1.63	0.6	20	160	< 0.5	< 2	0.74	0.5	16	25	25	4.21	< 10	< 1	0.12	20	0.71	1710	1
24388	201 238	1.74	0.6	25	150	< 0.5	< 2	0.38	0.5	18	26	30	4.69	< 10	< 1	0.13	30	0.76	1985	1
24389	201 238	1.33	0.4	30	120	< 0.5	2	1.67	0.5	15	19	36	5.24	< 10	< 1	0.10	10	1.19	1975	1
24390	201 238	1.44	0.4	15	200	< 0.5	2	1.05	0.5	15	24	25	3.73	< 10	< 1	0.07	10	0.61	1910	1
24391	201 238	0.93	0.4	25	60	< 0.5	2	4.79	< 0.5	16	17	39	2.68	< 10	< 1	0.10	< 10	3.14	935	< 1
24392	201 238	0.93	0.4	20	60	< 0.5	6	4.05	< 0.5	18	16	38	2.85	< 10	< 1	0.12	< 10	2.87	1050	1
24393	201 238	1.50	0.4	30	120	< 0.5	2	1.84	0.5	20	22	28	3.93	< 10	< 1	0.32	10	1.83	1985	1
24394	201 238	2.15	0.8	20	150	< 0.5	< 2	2.74	0.5	24	25	54	3.19	< 10	< 1	0.49	< 10	3.34	700	1
24395	201 238	2.02	0.4	5	120	< 0.5	< 2	1.01	0.5	13	28	26	3.44	< 10	< 1	0.25	20	1.87	1185	< 1
24396	201 238	1.93	< 0.2	10	120	< 0.5	< 2	0.38	< 0.5	13	23	11	3.45	< 10	< 1	0.19	20	1.07	645	1
24397	201 238	1.46	0.2	20	150	< 0.5	< 2	0.72	1.0	16	23	26	4.16	< 10	< 1	0.12	20	0.72	1860	1
24398	201 238	1.62	0.2	15	130	< 0.5	< 2	0.53	< 0.5	15	25	30	4.20	< 10	< 1	0.16	20	1.12	1585	1
24399	201 238	1.37	0.2	15	120	< 0.5	2	0.78	0.5	13	21	18	4.00	< 10	< 1	0.10	20	0.86	1715	< 1
24400	201 238	1.14	0.4	25	100	< 0.5	4	0.75	< 0.5	20	17	44	4.20	< 10	< 1	0.12	20	0.90	2660	1
24401	217 238	1.20	0.4	25	70	< 0.5	2	1.83	< 0.5	17	93	31	2.96	< 10	< 1	0.38	10	1.35	1330	1
24402	203 238	1.35	0.4	25	90	< 0.5	2	2.52	0.5	17	128	42	3.37	< 10	< 1	0.47	< 10	1.84	1450	1
24403	201 238	0.98	0.4	20	80	< 0.5	< 2	3.14	0.5	20	15	49	3.61	< 10	< 1	0.12	< 10	1.88	1525	1
24404	201 238	1.03	0.4	25	80	< 0.5	2	2.57	0.5	19	15	44	3.62	< 10	< 1	0.16	< 10	1.90	1495	1
24405	201 238	1.55	0.6	30	170	< 0.5	4	1.03	1.0	20	28	46	4.26	< 10	< 1	0.09	10	0.72	1860	1
24406	201 238	1.22	0.6	30	150	< 0.5	4	1.61	1.5	15	22	36	3.40	< 10	< 1	0.10	10	0.66	1725	1
24407	201 238	1.56	0.6	25	170	< 0.5	2	1.04	1.0	14	26	37	4.08	< 10	< 1	0.07	20	0.67	1535	1
24408	203 238	2.16	< 0.2	25	260	< 0.5	2	0.21	0.5	16	95	33	4.94	< 10	< 1	0.43	30	0.59	1565	2
24409	201 238	1.55	0.2	35	130	< 0.5	2	0.51	0.5	15	25	41	5.41	< 10	< 1	0.08	20	0.62	1830	2

CERTIFICATION :

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

I. ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24370	201 238	< 0.01	32	570	118	5	5	8	0.01	< 10	< 10	23	< 10	1895
24371	201 238	< 0.01	78	310	134	15	4	13	< 0.01	< 10	< 10	13	10	5380
24372	201 238	< 0.01	91	400	178	15	4	9	< 0.01	< 10	< 10	15	10	6220
24373	201 238	< 0.01	32	340	142	10	3	16	< 0.01	< 10	< 10	9	< 10	6680
24374	201 238	< 0.01	66	310	1620	15	3	18	< 0.01	< 10	< 10	6	10	7640
24375	201 238	0.01	83	200	248	10	3	16	< 0.01	< 10	< 10	11	10	6040
24376	201 238	0.01	32	320	150	10	3	27	< 0.01	< 10	< 10	8	10	7590
24377	201 238	< 0.01	52	290	108	10	4	15	< 0.01	< 10	< 10	8	10	8930
24378	201 238	0.01	93	550	398	15	5	8	0.01	< 10	< 10	17	10	>10000
24379	201 238	0.01	58	430	114	10	5	11	0.01	< 10	< 10	17	< 10	5090
24380	201 238	< 0.01	64	680	192	10	7	10	0.02	< 10	< 10	28	< 10	6610
24381	201 238	< 0.01	24	880	100	< 5	7	11	0.03	< 10	< 10	41	< 10	1200
24382	201 238	< 0.01	31	630	42	< 5	6	7	0.02	< 10	< 10	39	< 10	794
24383	201 238	< 0.01	27	860	56	< 5	6	8	0.02	< 10	< 10	41	< 10	680
24384	201 238	< 0.01	44	390	134	< 5	13	8	0.02	< 10	< 10	43	< 10	1125
24385	201 238	0.01	35	740	82	5	6	15	0.02	< 10	< 10	33	< 10	1510
24386	201 238	< 0.01	25	840	86	5	5	10	0.01	< 10	< 10	40	< 10	1090
24387	201 238	< 0.01	28	660	44	< 5	6	10	0.02	< 10	< 10	39	< 10	560
24388	201 238	< 0.01	30	480	48	< 5	7	10	0.03	< 10	< 10	39	< 10	412
24389	201 238	< 0.01	25	750	62	5	8	11	0.02	< 10	< 10	32	< 10	586
24390	201 238	< 0.01	18	810	146	< 5	4	15	0.03	< 10	< 10	40	< 10	392
24391	201 238	0.01	24	720	30	5	4	24	0.04	< 10	< 10	28	< 10	194
24392	201 238	0.01	24	740	34	5	4	18	0.03	< 10	< 10	26	< 10	296
24393	201 238	0.01	24	740	102	< 5	6	13	0.03	< 10	< 10	31	< 10	498
24394	201 238	0.01	29	630	402	< 5	5	19	0.03	< 10	< 10	28	< 10	578
24395	201 238	0.01	25	740	64	< 5	6	13	0.04	< 10	< 10	35	< 10	390
24396	201 238	< 0.01	18	370	42	< 5	4	11	0.03	< 10	< 10	38	< 10	350
24397	201 238	< 0.01	26	880	50	< 5	5	11	0.03	< 10	< 10	36	< 10	848
24398	201 238	< 0.01	27	410	78	< 5	7	10	0.02	< 10	< 10	35	< 10	374
24399	201 238	< 0.01	20	710	50	< 5	5	10	0.02	< 10	< 10	31	< 10	308
24400	201 238	< 0.01	25	530	54	< 5	6	9	0.02	< 10	< 10	25	< 10	350
24401	217 238	0.01	24	670	52	5	4	11	0.01	< 10	< 10	22	< 10	258
24402	203 238	0.02	28	740	48	5	5	15	0.02	< 10	< 10	26	10	254
24403	201 238	< 0.01	28	750	60	5	4	18	0.02	< 10	< 10	23	< 10	274
24404	201 238	< 0.01	27	910	86	< 5	5	15	0.02	< 10	< 10	25	< 10	404
24405	201 238	< 0.01	27	980	244	5	4	14	0.02	< 10	< 10	37	< 10	1475
24406	201 238	< 0.01	19	900	210	< 5	3	16	0.02	< 10	< 10	29	< 10	1285
24407	201 238	< 0.01	27	710	234	< 5	5	15	0.03	< 10	< 10	40	< 10	884
24408	203 238	0.01	26	490	220	5	5	11	0.03	< 10	< 10	60	< 10	570
24409	201 238	< 0.01	25	570	344	5	6	9	0.01	< 10	< 10	38	< 10	756

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER
BRITISH COLUMBIA CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE. BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24410	201 238	1.68	< 0.2	15	200	< 0.5	< 2	0.57	< 0.5	15	25	16	5.19	< 10	< 1	0.06	20	0.51	1905	1
24411	201 238	1.32	0.4	15	130	< 0.5	2	1.44	0.5	16	24	33	4.00	< 10	< 1	0.08	20	1.25	1530	1
24412	201 238	1.47	0.8	20	110	0.5	2	1.27	0.5	16	23	25	5.08	< 10	< 1	0.13	20	1.22	2320	< 1
24413	201 238	0.89	0.6	25	90	< 0.5	4	3.59	0.5	20	13	29	4.60	< 10	< 1	0.09	< 10	2.32	3430	1
24414	201 238	0.67	0.8	30	80	< 0.5	2	7.20	0.5	23	11	39	3.84	< 10	< 1	0.08	< 10	4.36	2740	< 1
24415	201 238	1.21	1.4	45	120	0.5	4	2.07	3.0	21	24	47	5.25	< 10	< 1	0.08	10	1.54	2600	2
24416	201 238	0.92	1.4	50	130	< 0.5	2	4.16	4.0	19	24	39	4.44	< 10	< 1	0.07	< 10	2.67	2690	2
24417	201 238	0.73	1.6	85	80	< 0.5	4	6.03	4.5	21	15	45	4.31	< 10	< 1	0.07	< 10	3.75	1985	1
24418	201 238	0.53	2.8	80	40	< 0.5	< 2	7.58	12.5	23	10	54	3.66	< 10	< 1	0.07	< 10	4.43	1690	1
24419	201 238	0.53	1.8	125	40	< 0.5	4	7.02	11.0	23	10	50	4.18	< 10	< 1	0.08	< 10	4.19	1385	2
24420	201 238	0.67	4.4	95	40	< 0.5	4	6.93	18.0	25	13	57	3.86	< 10	< 1	0.08	< 10	4.19	1430	1
24421	201 238	0.72	4.0	95	40	< 0.5	4	5.73	18.0	19	12	49	3.80	< 10	< 1	0.08	< 10	3.47	1515	1
24422	201 238	0.52	4.0	90	30	< 0.5	< 2	6.17	17.5	23	9	63	3.41	< 10	< 1	0.08	< 10	3.71	1235	1
24423	201 238	0.80	6.0	145	40	< 0.5	4	5.25	20.0	23	15	58	5.24	< 10	< 1	0.07	< 10	3.47	1235	2
24424	201 238	0.71	4.8	90	40	< 0.5	4	4.58	17.0	23	15	50	4.47	< 10	< 1	0.05	< 10	2.87	1690	2
24425	201 238	0.38	8.0	75	20	< 0.5	4	5.21	20.0	20	6	42	3.01	< 10	< 1	0.04	< 10	3.06	1315	1
24426	201 238	0.43	7.4	155	20	< 0.5	4	6.09	10.0	23	9	48	4.97	< 10	< 1	0.03	< 10	3.62	1515	3
24427	201 238	0.46	2.8	140	40	< 0.5	< 2	5.77	6.0	26	11	46	5.25	< 10	< 1	0.05	< 10	3.42	1910	3
24428	201 238	0.56	3.8	120	40	< 0.5	4	4.52	7.0	26	13	48	5.35	< 10	< 1	0.05	< 10	2.73	1695	2
24429	201 238	0.71	6.6	230	20	< 0.5	6	6.81	46.5	22	15	57	4.55	< 10	< 1	0.04	< 10	4.61	915	3
24430	201 238	0.25	5.8	180	20	< 0.5	2	7.19	37.0	27	6	138	3.91	< 10	< 1	0.04	< 10	4.06	1125	1
24431	201 238	0.40	9.0	270	20	< 0.5	6	6.60	34.0	29	9	74	6.12	< 10	< 1	0.05	< 10	3.80	1860	2
24432	201 238	0.63	7.2	155	40	< 0.5	6	7.04	43.0	27	11	92	4.98	< 10	< 1	0.07	< 10	4.15	1665	2
24433	201 238	0.59	4.4	135	30	< 0.5	4	6.36	24.0	27	10	64	4.49	< 10	< 1	0.07	< 10	3.68	1820	1
24434	201 238	1.00	3.0	130	80	< 0.5	4	3.73	12.5	25	17	60	5.59	< 10	< 1	0.09	< 10	2.35	1665	2
24435	201 238	0.55	1.2	80	40	< 0.5	2	6.95	5.0	25	10	99	3.24	< 10	< 1	0.08	< 10	4.00	1290	1
24436	201 238	0.97	1.2	30	100	< 0.5	6	6.46	2.5	17	20	39	3.80	< 10	< 1	0.11	< 10	3.97	1945	1
24437	201 238	1.27	1.8	65	90	< 0.5	2	0.65	2.0	22	19	29	5.38	< 10	< 1	0.13	20	0.62	1895	1
24438	201 238	0.84	1.2	45	120	0.5	4	4.00	1.5	27	16	74	4.17	< 10	< 1	0.10	< 10	2.34	2440	< 1
24439	201 238	1.25	1.4	45	110	0.5	4	1.63	2.0	22	21	53	5.25	< 10	< 1	0.10	10	1.27	1990	2
24440	201 238	1.19	1.0	45	120	< 0.5	< 2	0.65	1.5	16	22	36	4.59	< 10	< 1	0.09	20	0.63	1450	2
24441	201 238	1.14	1.0	30	160	< 0.5	< 2	0.72	2.0	22	20	59	5.20	< 10	< 1	0.09	20	0.62	2780	1
24442	201 238	1.06	0.6	40	130	< 0.5	2	1.48	1.5	22	21	47	5.16	< 10	< 1	0.07	10	0.90	3300	1
24443	201 238	1.23	0.6	30	130	< 0.5	2	0.64	1.0	18	27	39	4.82	< 10	< 1	0.07	20	0.61	2340	1
24444	201 238	1.44	0.8	30	160	0.5	2	0.76	1.5	15	23	24	5.38	< 10	< 1	0.05	20	0.55	3090	2
24445	201 238	1.42	0.8	25	150	0.5	6	0.74	1.5	21	24	32	4.98	< 10	< 1	0.09	20	0.58	2690	1
24446	201 238	1.59	0.8	40	150	0.5	< 2	0.85	1.0	19	26	37	4.74	< 10	< 1	0.10	20	0.69	2170	2
24447	201 238	0.64	0.6	25	120	< 0.5	< 2	5.28	< 0.5	19	10	41	3.15	< 10	< 1	0.11	< 10	3.05	1330	1
24448	217 238	1.37	0.4	5	120	0.5	2	2.67	< 0.5	13	69	28	2.35	< 10	< 1	0.38	< 10	1.38	1200	< 1
24449	201 238	1.34	0.2	25	110	0.5	2	1.22	< 0.5	15	18	24	4.36	< 10	< 1	0.12	20	1.04	2170	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24410	201 238	< 0.01	16	570	252	< 5	3	10	0.02	< 10	< 10	44	< 10	588
24411	201 238	0.01	29	620	186	5	6	18	0.04	< 10	< 10	37	< 10	964
24412	201 238	< 0.01	27	590	152	5	8	11	0.02	< 10	< 10	30	< 10	720
24413	201 238	< 0.01	27	610	206	5	5	13	0.01	< 10	< 10	19	10	636
24414	201 238	0.01	25	540	160	5	5	23	0.01	< 10	< 10	17	10	902
24415	201 238	< 0.01	33	660	488	5	6	12	0.02	< 10	< 10	30	10	2930
24416	201 238	< 0.01	33	530	614	5	6	11	0.02	< 10	< 10	25	10	3170
24417	201 238	0.01	38	490	736	5	5	16	0.01	< 10	< 10	20	10	3640
24418	201 238	< 0.01	34	450	978	5	4	30	0.01	< 10	< 10	15	10	6830
24419	201 238	< 0.01	38	410	420	5	4	20	0.01	< 10	< 10	15	10	6650
24420	201 238	0.01	48	490	2390	5	5	40	0.01	< 10	< 10	19	20	>10000
24421	201 238	0.01	35	480	1840	5	5	23	0.01	< 10	< 10	19	20	>10000
24422	201 238	< 0.01	34	420	1530	10	5	37	0.01	< 10	< 10	14	10	>10000
24423	201 238	< 0.01	52	440	2910	10	6	24	0.01	< 10	< 10	20	20	>10000
24424	201 238	< 0.01	48	440	3370	5	5	21	0.01	< 10	< 10	21	20	9100
24425	201 238	< 0.01	23	560	5450	5	4	29	< 0.01	< 10	< 10	10	20	>10000
24426	201 238	< 0.01	49	350	5510	15	4	32	< 0.01	< 10	< 10	12	20	7620
24427	201 238	< 0.01	57	290	766	10	6	28	< 0.01	< 10	< 10	17	10	3720
24428	201 238	< 0.01	55	390	1845	10	5	17	0.01	< 10	< 10	18	10	5040
24429	201 238	< 0.01	33	350	1465	10	3	21	< 0.01	< 10	< 10	12	30	>10000
24430	201 238	< 0.01	44	390	566	15	4	37	< 0.01	< 10	< 10	7	20	>10000
24431	201 238	< 0.01	51	390	4360	15	4	17	< 0.01	< 10	< 10	12	30	>10000
24432	201 238	0.01	52	530	1575	10	4	19	0.01	< 10	< 10	16	30	>10000
24433	201 238	0.01	48	460	1645	10	5	24	0.01	< 10	< 10	16	20	>10000
24434	201 238	< 0.01	48	630	884	10	6	13	0.01	< 10	< 10	25	20	8890
24435	201 238	< 0.01	36	450	270	5	4	29	0.01	< 10	< 10	15	< 10	3530
24436	201 238	0.01	30	540	532	5	5	21	0.02	< 10	< 10	25	< 10	2260
24437	201 238	< 0.01	24	750	986	5	6	9	0.02	< 10	< 10	30	< 10	1720
24438	201 238	< 0.01	28	650	354	5	6	19	0.01	< 10	< 10	21	10	1820
24439	201 238	< 0.01	31	680	422	5	8	11	0.02	< 10	< 10	28	< 10	2410
24440	201 238	< 0.01	27	750	300	< 5	6	9	0.02	< 10	< 10	26	< 10	1940
24441	201 238	< 0.01	30	690	404	< 5	6	10	0.02	< 10	< 10	28	< 10	1870
24442	201 238	< 0.01	25	780	260	5	6	12	0.02	< 10	< 10	26	< 10	1100
24443	201 238	< 0.01	31	690	184	5	7	12	0.03	< 10	< 10	33	< 10	1290
24444	201 238	< 0.01	22	830	370	< 5	6	13	0.03	< 10	< 10	38	< 10	1230
24445	201 238	< 0.01	26	940	272	< 5	6	12	0.02	< 10	< 10	37	< 10	1210
24446	201 238	< 0.01	26	980	280	5	6	14	0.02	< 10	< 10	39	< 10	1315
24447	201 238	0.01	22	590	30	5	4	21	0.01	< 10	< 10	17	< 10	168
24448	217 238	0.01	16	830	40	< 5	3	17	0.01	< 10	< 10	21	< 10	238
24449	201 238	< 0.01	21	830	88	5	5	12	0.02	< 10	< 10	30	< 10	370

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3123 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24450	201	238	1.38	0.6	30	190	< 0.5	6	0.73	< 0.5	17	23	39	4.89	< 10	< 1	0.09	20	0.85	2090	1
24451	201	238	1.09	0.2	15	80	< 0.5	4	3.45	< 0.5	21	27	50	3.44	< 10	< 1	0.08	< 10	2.31	1495	< 1
24452	201	238	1.11	0.2	25	90	< 0.5	2	1.34	< 0.5	18	27	48	4.21	< 10	< 1	0.07	10	1.21	1900	< 1
24453	201	238	1.23	< 0.2	25	130	< 0.5	8	0.77	< 0.5	20	27	47	4.70	< 10	< 1	0.06	20	0.77	2250	< 1
24454	201	238	1.40	< 0.2	30	140	< 0.5	4	0.54	< 0.5	23	26	39	5.19	< 10	< 1	0.08	20	0.70	2980	< 1
24455	201	238	1.18	0.8	30	50	< 0.5	8	3.78	0.5	25	31	82	4.18	< 10	< 1	0.06	< 10	3.11	2100	< 1
24456	201	238	1.30	0.8	40	140	< 0.5	4	0.71	2.0	14	23	22	4.94	< 10	< 1	0.07	20	0.52	2200	< 1
24457	201	238	1.38	0.8	25	150	< 0.5	6	0.98	2.0	14	24	26	4.99	< 10	< 1	0.07	20	0.74	2060	1
24458	201	238	1.45	1.4	35	140	< 0.5	4	0.60	1.0	14	26	25	5.01	< 10	< 1	0.07	20	0.57	2010	1
24459	201	238	1.42	0.8	35	130	0.5	4	0.51	1.0	14	24	21	4.91	< 10	< 1	0.06	20	0.50	2180	2
24460	201	238	1.15	1.2	40	130	< 0.5	< 2	0.53	2.0	14	20	18	5.89	< 10	< 1	0.06	30	0.41	2810	1
24504	201	238	1.16	0.2	20	130	< 0.5	6	1.77	< 0.5	20	26	53	4.67	< 10	< 1	0.07	10	1.29	2500	< 1
24505	201	238	1.12	0.4	35	170	< 0.5	6	1.61	< 0.5	19	25	50	4.68	< 10	< 1	0.08	10	1.15	2660	< 1
24506	201	238	1.26	0.4	25	80	< 0.5	6	2.87	< 0.5	24	30	69	4.14	< 10	< 1	0.08	< 10	2.36	1770	< 1
24507	201	238	1.64	0.2	25	260	< 0.5	4	1.12	< 0.5	13	29	23	4.73	< 10	< 1	0.05	20	0.74	2510	2
24508	201	238	1.81	0.4	20	280	0.5	6	0.66	< 0.5	16	31	28	5.74	< 10	< 1	0.07	20	0.56	3690	1
24509	217	238	1.67	< 0.2	20	200	< 0.5	4	0.38	< 0.5	17	127	24	5.35	< 10	< 1	0.23	20	0.58	1730	1
24510	201	238	1.46	0.2	15	150	< 0.5	4	0.47	0.5	14	27	13	5.55	< 10	< 1	0.07	20	0.31	2780	2
24511	201	238	1.14	0.4	25	270	< 0.5	6	1.25	0.5	14	20	28	5.16	< 10	< 1	0.05	10	0.47	3810	1
24512	201	238	1.24	0.4	45	180	< 0.5	6	0.61	< 0.5	20	24	47	7.26	< 10	< 1	0.06	20	0.45	4330	4
24513	201	238	1.49	0.4	30	220	< 0.5	4	1.00	< 0.5	14	26	24	4.47	< 10	< 1	0.05	10	0.56	2380	2
24514	201	238	1.43	0.6	35	220	< 0.5	4	0.65	< 0.5	17	26	46	7.25	< 10	< 1	0.06	20	0.55	4570	3
24515	201	238	1.05	0.6	35	200	< 0.5	4	2.34	< 0.5	17	20	49	5.15	< 10	< 1	0.08	< 10	1.43	3030	2
24516	201	238	0.70	0.6	25	130	< 0.5	6	5.33	< 0.5	16	12	45	3.84	< 10	< 1	0.09	< 10	3.15	2650	1
24517	201	238	1.03	0.4	25	170	< 0.5	4	1.34	< 0.5	15	19	33	4.73	< 10	< 1	0.07	10	0.92	2740	1
24518	201	238	0.67	0.6	15	140	< 0.5	6	5.48	0.5	15	13	45	4.24	< 10	< 1	0.05	< 10	3.23	3300	2
24519	201	238	0.49	0.6	35	110	< 0.5	4	6.89	< 0.5	21	10	21	4.51	< 10	< 1	0.05	< 10	3.56	3770	< 1
24520	201	238	0.93	0.8	30	160	< 0.5	6	2.78	0.5	15	17	32	4.86	< 10	< 1	0.07	< 10	1.68	3090	1
24521	201	238	0.77	0.8	30	130	< 0.5	6	3.95	0.5	15	15	34	4.20	< 10	< 1	0.06	< 10	2.39	2770	1
24522	201	238	0.58	0.8	30	90	< 0.5	6	3.82	0.5	14	12	25	4.25	< 10	< 1	0.07	< 10	2.22	2530	< 1
24523	201	238	0.62	1.0	25	90	0.5	6	3.19	1.5	15	12	32	4.93	< 10	< 1	0.05	< 10	1.87	2730	< 1
24524	201	238	0.55	1.6	30	50	< 0.5	4	3.27	2.0	12	11	39	4.17	< 10	< 1	0.05	< 10	1.74	1235	< 1
24525	201	238	0.53	1.6	35	70	0.5	4	2.88	2.0	16	11	32	3.96	< 10	< 1	0.05	< 10	1.53	1590	1
24526	201	238	0.80	0.6	30	60	0.5	2	0.79	< 0.5	13	16	41	5.19	< 10	< 1	0.05	20	0.60	1845	< 1
24527	201	238	1.08	0.6	30	90	< 0.5	< 2	0.81	< 0.5	19	22	52	4.35	< 10	< 1	0.07	20	0.60	1960	< 1
24528	201	238	0.55	0.8	30	100	< 0.5	4	3.39	0.5	17	12	34	4.55	< 10	< 1	0.07	< 10	1.96	2910	< 1
24529	201	238	0.84	1.2	35	100	0.5	6	3.25	< 0.5	20	13	30	4.12	< 10	< 1	0.08	< 10	2.29	2540	< 1
24530	201	238	0.59	3.6	45	80	< 0.5	6	5.12	2.5	20	11	42	4.19	< 10	< 1	0.06	< 10	3.04	2450	1
24531	201	238	0.42	0.8	35	90	0.5	2	4.82	< 0.5	24	9	29	3.72	< 10	< 1	0.06	< 10	2.68	2270	< 1
24532	201	238	0.44	0.6	30	90	0.5	2	5.78	< 0.5	23	10	27	3.83	< 10	< 1	0.04	< 10	3.29	2330	< 1

CERTIFICATION :

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page i : 3-B
Tot. Pages: 5
Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24450	201 238	0.01	33	730	80	< 5	6	13	0.03	< 10	< 10	36	< 10	396
24451	201 238	0.01	27	910	24	< 5	6	27	0.05	< 10	< 10	40	< 10	126
24452	201 238	< 0.01	26	770	20	< 5	7	14	0.04	< 10	< 10	41	< 10	130
24453	201 238	< 0.01	27	690	32	< 5	7	13	0.03	< 10	< 10	41	< 10	140
24454	201 238	< 0.01	31	930	52	< 5	7	11	0.03	< 10	< 10	39	< 10	184
24455	201 238	0.01	37	830	304	< 5	7	21	0.03	< 10	< 10	41	< 10	806
24456	201 238	0.01	25	740	604	< 5	6	15	0.03	< 10	< 10	38	< 10	1690
24457	201 238	0.01	24	730	442	5	7	16	0.03	< 10	< 10	42	< 10	1765
24458	201 238	0.01	26	660	808	< 5	7	15	0.03	< 10	< 10	43	< 10	1640
24459	201 238	< 0.01	26	620	420	5	7	15	0.03	< 10	< 10	40	< 10	1390
24460	201 238	< 0.01	23	650	618	< 5	7	12	0.02	< 10	< 10	34	< 10	1900
24504	201 238	0.01	31	790	38	5	6	19	0.04	< 10	< 10	44	< 10	158
24505	201 238	0.01	31	850	26	5	6	15	0.03	< 10	< 10	39	< 10	144
24506	201 238	0.01	34	840	104	< 5	7	21	0.04	< 10	< 10	42	< 10	370
24507	201 238	0.01	22	800	74	< 5	5	18	0.05	< 10	< 10	50	< 10	196
24508	201 238	0.01	28	910	114	< 5	6	16	0.04	< 10	< 10	52	< 10	254
24509	217 238	0.01	30	480	80	< 5	5	11	0.03	< 10	< 10	52	< 10	252
24510	201 238	< 0.01	13	770	164	5	4	12	0.04	< 10	< 10	54	< 10	380
24511	201 238	< 0.01	25	940	140	< 5	4	14	0.02	< 10	< 10	35	< 10	404
24512	201 238	< 0.01	36	640	154	5	7	10	0.02	< 10	< 10	40	< 10	440
24513	201 238	< 0.01	20	1080	80	< 5	4	14	0.03	< 10	< 10	40	< 10	230
24514	201 238	< 0.01	33	790	106	< 5	7	11	0.03	< 10	< 10	44	< 10	332
24515	201 238	0.01	30	790	120	< 5	5	16	0.02	< 10	< 10	32	< 10	380
24516	201 238	0.01	23	640	152	5	4	26	0.01	< 10	< 10	21	< 10	426
24517	201 238	< 0.01	26	660	188	5	5	12	0.02	< 10	< 10	30	< 10	450
24518	201 238	0.01	25	630	142	5	4	17	0.01	< 10	< 10	22	< 10	312
24519	201 238	0.01	27	620	120	5	4	32	0.01	< 10	< 10	16	< 10	248
24520	201 238	0.01	27	750	266	5	5	17	0.02	< 10	< 10	29	< 10	710
24521	201 238	0.01	25	690	218	5	5	23	0.02	< 10	< 10	24	< 10	556
24522	201 238	0.01	21	740	234	5	5	33	0.01	< 10	< 10	20	< 10	788
24523	201 238	< 0.01	23	750	548	5	5	27	0.01	< 10	< 10	19	< 10	1370
24524	201 238	< 0.01	22	1020	1185	5	4	27	< 0.01	< 10	< 10	18	< 10	2110
24525	201 238	< 0.01	24	880	990	10	4	42	< 0.01	< 10	< 10	16	< 10	1665
24526	201 238	< 0.01	20	630	278	5	6	14	0.01	< 10	< 10	23	< 10	538
24527	201 238	< 0.01	27	770	242	5	5	16	0.02	< 10	< 10	33	< 10	502
24528	201 238	< 0.01	20	700	142	5	5	31	< 0.01	< 10	< 10	17	< 10	638
24529	201 238	< 0.01	24	720	196	5	6	20	0.01	< 10	< 10	20	< 10	430
24530	201 238	0.01	27	700	2110	10	4	34	0.01	< 10	< 10	19	< 10	2540
24531	201 238	< 0.01	30	660	146	10	4	39	< 0.01	< 10	< 10	13	< 10	414
24532	201 238	0.01	28	620	128	10	4	48	< 0.01	< 10	< 10	16	< 10	262

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J 2C1
PHONE (604) 984-0221

I RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24533	201 238	0.56	4.8	55	60	1.0	4	2.17	5.0	29	10	38	5.18	< 10	< 1	0.08	< 10	1.23	1865	< 1
24534	201 238	0.46	2.8	40	50	< 0.5	6	5.53	5.5	15	13	36	4.25	< 10	< 1	0.05	< 10	3.26	2100	< 1
24535	201 238	0.51	1.4	30	60	< 0.5	2	5.37	2.5	16	12	28	4.02	< 10	< 1	0.05	< 10	3.22	2310	< 1
24536	201 238	0.52	0.6	20	50	0.5	4	1.59	0.5	15	10	21	4.01	< 10	< 1	0.08	10	0.86	1310	< 1
24537	201 238	0.58	0.8	35	80	0.5	2	3.26	0.5	15	12	28	4.39	< 10	< 1	0.06	< 10	1.86	2640	< 1
24538	201 238	0.86	0.6	30	170	0.5	4	3.70	< 0.5	17	19	42	5.02	< 10	< 1	0.05	< 10	2.24	3410	3
24539	201 238	0.76	0.6	25	160	< 0.5	6	1.73	< 0.5	18	13	31	4.86	< 10	< 1	0.07	10	0.97	3220	1
24540	201 238	0.79	0.6	30	130	0.5	6	2.17	< 0.5	23	15	31	4.56	< 10	< 1	0.08	< 10	1.26	2360	3
24541	201 238	0.50	0.6	25	80	< 0.5	8	6.92	< 0.5	24	13	20	5.23	< 10	< 1	0.07	< 10	3.58	3870	1
24542	201 238	2.19	0.2	15	130	0.5	6	0.84	< 0.5	24	28	28	6.68	< 10	< 1	0.10	30	1.04	1660	1
24543	201 238	1.46	0.4	30	190	< 0.5	4	1.11	0.5	17	22	29	6.73	< 10	< 1	0.06	20	0.51	3280	2
24544	201 238	1.51	0.6	25	190	0.5	2	0.99	0.5	16	22	28	6.32	< 10	< 1	0.07	20	0.48	4040	1
24545	201 238	1.43	0.4	35	180	< 0.5	6	0.99	< 0.5	15	27	42	6.08	< 10	< 1	0.07	20	0.74	2760	3
24546	201 238	1.29	0.6	35	220	0.5	6	0.62	0.5	17	20	26	5.72	< 10	< 1	0.06	20	0.44	3690	2
24547	201 238	1.44	0.6	40	160	< 0.5	2	0.62	< 0.5	16	26	37	7.64	< 10	< 1	0.05	20	0.47	3180	3
24548	201 238	1.12	0.6	40	180	< 0.5	6	0.59	0.5	17	19	34	5.90	< 10	< 1	0.04	20	0.45	3470	3
24549	201 238	1.88	0.2	25	230	< 0.5	2	0.56	< 0.5	14	31	17	5.31	< 10	< 1	0.05	20	0.55	1865	2
24550	201 238	1.40	0.4	10	280	< 0.5	2	1.31	0.5	14	22	30	4.98	< 10	< 1	0.04	10	0.59	3430	2
24551	201 238	1.35	0.2	15	270	< 0.5	2	1.11	0.5	14	24	21	4.05	< 10	< 1	0.05	10	0.52	2000	1
24552	201 238	1.42	0.6	35	150	< 0.5	6	0.73	0.5	24	38	79	5.72	< 10	< 1	0.07	20	1.16	3180	1
24553	201 238	1.07	0.2	15	80	< 0.5	6	3.79	< 0.5	21	32	56	3.60	< 10	< 1	0.07	< 10	2.66	1710	< 1
24554	201 238	1.17	0.2	20	120	< 0.5	4	2.70	< 0.5	22	28	61	3.95	< 10	< 1	0.08	< 10	2.01	1680	< 1
24555	201 238	1.04	0.2	15	120	< 0.5	2	2.87	< 0.5	20	27	49	3.78	< 10	< 1	0.08	< 10	2.00	1560	< 1
24556	201 238	1.20	0.2	15	150	< 0.5	< 2	1.04	< 0.5	20	25	46	4.87	< 10	< 1	0.07	20	1.15	3170	< 1
24557	201 238	1.08	0.2	20	70	< 0.5	2	3.46	< 0.5	21	30	57	3.87	< 10	< 1	0.07	< 10	2.53	2020	< 1
24558	201 238	1.12	< 0.2	15	80	< 0.5	4	3.04	< 0.5	22	29	54	4.10	< 10	< 1	0.08	< 10	2.30	2040	< 1
24559	201 238	1.40	0.2	15	140	< 0.5	4	1.08	< 0.5	19	26	25	4.48	< 10	< 1	0.08	10	0.79	3010	< 1
24560	201 238	1.16	< 0.2	30	100	< 0.5	2	0.61	< 0.5	21	22	30	4.93	< 10	< 1	0.09	20	0.66	2720	1
24561	201 238	1.12	0.6	25	120	< 0.5	4	2.59	< 0.5	21	26	52	4.56	< 10	< 1	0.11	< 10	1.92	2320	1
24562	201 238	1.15	0.2	15	110	< 0.5	4	1.78	0.5	15	26	45	3.29	< 10	< 1	0.13	< 10	0.89	1960	< 1
24563	201 238	1.03	0.2	< 5	80	< 0.5	4	1.03	0.5	12	17	28	3.12	< 10	< 1	0.19	20	0.87	1425	< 1
24564	201 238	0.69	0.6	25	120	< 0.5	2	1.77	0.5	18	16	27	4.73	< 10	< 1	0.09	10	1.09	3240	< 1
24565	201 238	0.55	1.2	20	90	< 0.5	4	2.49	0.5	17	11	29	4.56	< 10	< 1	0.09	< 10	1.41	3400	1
24566	201 238	0.51	1.0	40	120	< 0.5	6	2.94	0.5	22	12	27	5.91	< 10	< 1	0.05	< 10	1.70	4650	1
24567	201 238	0.85	0.8	40	110	< 0.5	4	1.83	1.0	18	22	26	5.95	< 10	< 1	0.06	10	0.89	4180	2
24568	201 238	1.03	0.8	25	120	< 0.5	2	1.11	3.0	16	21	27	5.16	< 10	< 1	0.06	20	0.59	2660	1
24569	201 238	0.73	0.8	25	80	< 0.5	2	2.99	1.0	13	16	22	3.99	< 10	< 1	0.05	< 10	1.90	1810	< 1
24570	201 238	0.85	2.0	30	80	< 0.5	2	2.75	2.0	16	23	27	3.84	< 10	< 1	0.05	< 10	1.78	1745	1
24571	201 238	1.05	1.2	15	120	< 0.5	2	1.36	2.0	14	20	23	4.84	< 10	< 1	0.06	20	0.84	2720	1
24572	201 238	1.14	1.6	10	100	< 0.5	2	0.49	2.5	14	23	24	5.16	< 10	< 1	0.04	30	0.40	1895	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24533	201 238	< 0.01	31	730	2640	15	6	38	0.01	< 10	< 10	17	< 10	4210
24534	201 238	0.01	25	700	2280	5	4	37	0.01	< 10	< 10	16	< 10	3910
24535	201 238	0.01	21	590	678	5	5	34	0.01	< 10	< 10	18	< 10	1770
24536	201 238	< 0.01	19	780	264	< 5	5	29	< 0.01	< 10	< 10	15	< 10	782
24537	201 238	< 0.01	25	750	306	5	5	31	0.01	< 10	< 10	19	< 10	1080
24538	201 238	< 0.01	30	870	170	5	5	22	0.01	< 10	< 10	27	< 10	504
24539	201 238	< 0.01	28	930	126	5	4	15	0.01	< 10	< 10	22	< 10	378
24540	201 238	< 0.01	38	910	116	5	5	16	0.01	< 10	< 10	21	< 10	280
24541	201 238	0.01	30	1020	48	5	5	56	< 0.01	< 10	< 10	22	< 10	170
24542	201 238	< 0.01	24	850	68	< 5	11	16	0.09	< 10	< 10	97	< 10	216
24543	201 238	< 0.01	24	1330	180	5	6	16	0.02	< 10	< 10	40	< 10	706
24544	201 238	< 0.01	23	1250	220	5	5	14	0.03	< 10	< 10	38	< 10	574
24545	201 238	< 0.01	32	820	112	5	7	12	0.03	< 10	< 10	43	< 10	372
24546	201 238	< 0.01	25	790	266	5	6	11	0.03	< 10	< 10	37	< 10	788
24547	201 238	< 0.01	30	860	198	5	6	9	0.02	< 10	< 10	47	< 10	612
24548	201 238	< 0.01	28	580	272	< 5	6	10	0.02	< 10	< 10	35	< 10	718
24549	201 238	< 0.01	21	900	108	< 5	6	13	0.04	< 10	< 10	50	< 10	504
24550	201 238	0.01	23	1070	142	< 5	4	17	0.03	< 10	< 10	36	< 10	460
24551	201 238	0.01	21	1000	172	< 5	4	16	0.03	< 10	< 10	37	< 10	448
24552	201 238	< 0.01	38	540	238	< 5	9	11	0.04	< 10	< 10	51	< 10	738
24553	201 238	0.01	30	830	28	< 5	6	26	0.04	< 10	< 10	37	< 10	166
24554	201 238	0.01	32	850	22	< 5	6	23	0.04	< 10	< 10	40	< 10	164
24555	201 238	0.01	29	1010	14	< 5	6	25	0.04	< 10	< 10	39	< 10	126
24556	201 238	< 0.01	29	800	16	5	7	14	0.05	< 10	< 10	43	< 10	120
24557	201 238	0.01	30	780	26	5	7	23	0.04	< 10	< 10	36	< 10	134
24558	201 238	0.01	32	820	20	< 5	7	20	0.05	< 10	< 10	38	< 10	124
24559	201 238	< 0.01	22	1130	40	< 5	5	18	0.03	< 10	< 10	37	< 10	150
24560	201 238	< 0.01	30	820	24	< 5	6	13	0.02	< 10	< 10	31	< 10	136
24561	201 238	< 0.01	32	1040	80	5	6	23	0.02	< 10	< 10	35	< 10	250
24562	201 238	0.01	25	1430	70	< 5	4	19	0.03	< 10	< 10	34	< 10	400
24563	201 238	< 0.01	20	950	140	5	6	14	0.02	< 10	< 10	20	< 10	326
24564	201 238	< 0.01	29	860	236	5	6	15	0.01	< 10	< 10	22	< 10	542
24565	201 238	< 0.01	26	990	224	5	5	18	0.01	< 10	< 10	16	< 10	520
24566	201 238	< 0.01	36	760	308	5	5	20	0.01	< 10	< 10	21	< 10	752
24567	201 238	< 0.01	31	1030	330	5	5	19	0.01	< 10	< 10	30	< 10	952
24568	201 238	< 0.01	26	920	538	5	5	15	0.02	< 10	< 10	35	< 10	1720
24569	201 238	< 0.01	21	590	350	5	5	19	0.01	< 10	< 10	25	< 10	952
24570	201 238	0.01	26	700	912	5	6	23	0.02	< 10	< 10	29	< 10	1850
24571	201 238	< 0.01	22	780	730	5	6	14	0.02	< 10	< 10	32	< 10	1470
24572	201 238	< 0.01	24	510	944	5	7	13	0.03	< 10	< 10	36	< 10	1850

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # I-8920345
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24573	201 238	0.70	0.8	45	90	< 0.5	< 2	1.75	5.0	38	11	70	4.60	< 10	< 1	0.05	20	1.06	2270	1
24574	201 238	0.55	< 0.2	25	60	< 0.5	< 2	5.93	4.5	9	11	27	3.68	< 10	1	0.04	< 10	3.65	2290	< 1
24575	201 238	0.36	< 0.2	< 5	60	< 0.5	< 2	7.05	< 0.5	8	10	19	3.04	< 10	< 1	0.04	< 10	4.23	2460	< 1
24576	201 238	0.87	0.2	40	120	< 0.5	2	2.35	< 0.5	20	14	20	4.39	< 10	< 1	0.07	10	1.45	2240	1
24577	201 238	0.35	< 0.2	10	70	< 0.5	< 2	9.04	1.5	8	6	17	3.48	< 10	< 1	0.04	< 10	5.44	2750	< 1
24578	201 238	0.54	< 0.2	< 5	90	< 0.5	< 2	4.79	1.0	12	7	22	3.81	< 10	< 1	0.06	< 10	2.83	2700	< 1
24579	201 238	0.90	3.0	35	100	< 0.5	< 2	3.32	5.0	15	14	34	4.36	< 10	< 1	0.07	10	2.06	2520	< 1
24580	201 238	0.29	0.2	< 5	40	< 0.5	< 2	9.88	5.5	6	6	28	3.13	< 10	1	0.02	< 10	6.00	1940	< 1
24581	201 238	0.30	< 0.2	15	40	< 0.5	< 2	9.94	3.0	3	6	16	2.86	< 10	< 1	0.02	< 10	6.05	2190	< 1
24582	201 238	0.36	< 0.2	25	60	< 0.5	< 2	9.37	2.5	6	7	21	3.33	< 10	1	0.04	< 10	5.61	2590	< 1
24583	201 238	0.39	< 0.2	10	60	< 0.5	< 2	8.89	2.5	7	12	25	3.22	< 10	< 1	0.04	< 10	5.40	2460	< 1
24584	201 238	0.61	7.4	35	50	< 0.5	< 2	6.38	12.0	14	13	44	3.69	< 10	< 1	0.04	< 10	3.94	1715	< 1
24585	201 238	0.47	< 0.2	15	80	< 0.5	< 2	7.27	2.5	15	14	31	4.11	< 10	< 1	0.06	< 10	4.26	2690	< 1
24586	201 238	0.30	< 0.2	15	50	< 0.5	< 2	11.00	0.5	9	7	16	3.28	< 10	< 1	0.03	< 10	6.54	2050	< 1
24587	201 238	0.31	< 0.2	< 5	50	< 0.5	< 2	6.22	< 0.5	10	7	14	2.71	< 10	< 1	0.07	< 10	3.61	2030	< 1
24588	201 238	0.46	< 0.2	40	70	< 0.5	< 2	5.41	< 0.5	14	7	17	4.04	< 10	< 1	0.06	< 10	3.24	2050	< 1
24589	201 238	0.48	< 0.2	15	60	< 0.5	< 2	6.56	0.5	12	11	22	3.75	< 10	1	0.05	< 10	3.82	2240	< 1
24590	201 238	0.69	1.0	5	90	0.5	< 2	2.17	0.5	24	14	27	4.93	10	< 1	0.05	20	1.19	3410	< 1
24591	201 238	0.86	1.2	35	70	0.5	< 2	0.63	< 0.5	16	16	30	4.31	10	< 1	0.06	30	0.38	1545	< 1
24592	201 238	1.00	1.4	35	100	< 0.5	< 2	0.69	< 0.5	16	16	23	4.48	10	< 1	0.06	30	0.52	1735	1
24593	201 238	1.00	1.0	20	90	0.5	< 2	2.41	1.5	15	19	25	3.86	< 10	1	0.06	20	1.61	1560	1
24594	201 238	0.98	2.0	30	100	0.5	< 2	0.90	3.0	14	19	22	4.68	< 10	2	0.06	20	0.51	1815	1
24595	201 238	1.17	1.2	25	120	< 0.5	< 2	0.61	2.0	12	20	16	5.02	< 10	1	0.05	20	0.35	2860	1
24596	201 238	1.09	< 0.2	30	120	< 0.5	< 2	0.59	0.5	13	18	18	4.91	< 10	2	0.05	20	0.33	2550	1
24597	201 238	0.91	0.4	15	140	< 0.5	< 2	0.71	0.5	16	15	22	5.41	< 10	< 1	0.05	20	0.38	4050	< 1
24598	201 238	0.89	< 0.2	20	110	< 0.5	< 2	0.62	1.5	15	16	18	5.18	< 10	< 1	0.06	20	0.33	4450	< 1
24599	201 238	1.41	< 0.2	20	160	< 0.5	< 2	0.79	1.5	18	26	34	6.18	< 10	1	0.06	20	0.62	6260	1
24600	217 238	1.42	< 0.2	20	150	< 0.5	< 2	1.09	0.5	17	65	29	5.30	< 10	1	0.14	20	0.77	4490	1
24601	201 238	1.34	0.2	15	130	< 0.5	2	1.04	< 0.5	16	28	45	3.94	< 10	< 1	0.06	10	0.81	1980	< 1
24602	201 238	1.22	0.2	25	130	< 0.5	< 2	2.27	< 0.5	17	26	50	5.22	< 10	1	0.06	10	1.51	3390	1
24603	201 238	1.10	< 0.2	20	140	0.5	< 2	0.79	< 0.5	20	23	33	4.71	< 10	< 1	0.09	20	0.72	2860	1
24604	201 238	1.19	< 0.2	< 5	100	0.5	< 2	1.41	< 0.5	16	26	42	3.94	< 10	< 1	0.08	10	0.81	2100	< 1
24605	201 238	1.17	< 0.2	30	100	< 0.5	< 2	0.78	< 0.5	16	24	35	4.65	< 10	< 1	0.08	20	0.76	1780	< 1
24606	201 238	1.23	< 0.2	30	130	< 0.5	< 2	1.65	< 0.5	20	27	48	4.77	< 10	< 1	0.09	20	1.42	2750	< 1
24895	201 238	0.30	< 0.2	5	700	< 0.5	< 2	14.95	< 0.5	7	8	51	4.03	< 10	1	0.01	< 10	8.86	3420	< 1
24896	201 238	0.28	< 0.2	20	660	< 0.5	< 2	14.05	< 0.5	3	10	75	4.20	< 10	< 1	0.01	< 10	8.29	4490	1
24897	201 238	0.32	< 0.2	5	660	< 0.5	< 2	12.75	< 0.5	5	4	92	4.76	< 10	< 1	0.02	< 10	7.64	4810	1
24898	201 238	0.25	< 0.2	30	330	< 0.5	< 2	13.60	< 0.5	4	5	90	4.42	< 10	< 1	0.01	< 10	8.08	4110	2
24899	201 238	0.29	< 0.2	45	190	< 0.5	< 2	14.25	< 0.5	4	8	101	5.30	< 10	< 1	0.01	< 10	8.45	5030	< 1
24900	201 238	0.39	< 0.2	145	940	< 0.5	< 2	10.80	1.0	30	4	403	8.54	< 10	< 1	0.02	< 10	6.45	6410	< 1

CERTIFICATION :

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: CHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 25-JUL-89
Invoice # : I-8920345
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920345

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24573	201 238	< 0.01	37	640	494	5	6	19	0.01	< 10	< 10	20	< 10	4100
24574	201 238	0.01	14	580	1125	< 5	5	33	0.01	< 10	< 10	18	< 10	2970
24575	201 238	0.01	15	480	28	5	5	29	0.01	< 10	< 10	14	< 10	390
24576	201 238	< 0.01	30	720	114	5	6	30	0.02	< 10	< 10	26	< 10	706
24577	201 238	0.01	17	350	64	5	6	29	0.01	< 10	< 10	14	< 10	754
24578	201 238	0.01	20	530	130	5	6	17	0.01	< 10	< 10	19	< 10	636
24579	201 238	0.01	26	730	2380	5	6	15	0.02	< 10	< 10	28	< 10	4900
24580	201 238	0.01	14	290	3260	10	4	25	0.01	< 10	< 10	12	< 10	3070
24581	201 238	0.01	10	270	574	< 5	4	21	< 0.01	< 10	< 10	12	< 10	1440
24582	201 238	0.01	16	390	474	< 5	5	20	0.01	< 10	< 10	14	< 10	1270
24583	201 238	0.01	16	350	518	5	5	20	0.01	10	< 10	15	< 10	1450
24584	201 238	0.01	24	460	8120	15	5	23	0.02	10	< 10	20	< 10	8400
24585	201 238	0.01	22	490	574	10	6	31	0.01	10	< 10	18	< 10	1300
24586	201 238	0.01	17	250	188	10	5	47	0.01	10	< 10	15	< 10	706
24587	201 238	0.01	13	430	36	5	5	51	< 0.01	10	< 10	10	< 10	528
24588	201 238	0.01	19	500	84	10	5	42	0.01	10	< 10	16	< 10	712
24589	201 238	0.01	21	660	414	10	5	34	0.01	< 10	< 10	20	< 10	554
24590	201 238	< 0.01	34	720	320	10	6	37	0.01	< 10	< 10	26	< 10	1075
24591	201 238	< 0.01	28	490	420	5	6	17	0.02	10	< 10	27	< 10	840
24592	201 238	< 0.01	28	620	496	5	7	16	0.02	< 10	< 10	33	< 10	892
24593	201 238	0.01	25	630	858	5	6	24	0.03	< 10	< 10	32	< 10	1630
24594	201 238	< 0.01	25	880	1170	10	6	15	0.02	10	< 10	31	< 10	2180
24595	201 238	< 0.01	23	940	868	5	6	11	0.02	< 10	< 10	32	< 10	1590
24596	201 238	< 0.01	23	1080	366	5	5	11	0.02	< 10	< 10	33	< 10	798
24597	201 238	< 0.01	27	870	362	5	5	11	0.02	10	< 10	28	< 10	812
24598	201 238	< 0.01	20	840	670	5	5	9	0.02	10	< 10	26	< 10	1030
24599	201 238	0.01	27	1010	262	5	6	13	0.03	10	< 10	41	< 10	808
24600	217 238	0.01	28	1340	174	5	5	14	0.03	< 10	< 10	42	< 10	570
24601	201 238	< 0.01	28	1080	122	5	4	15	0.03	< 10	< 10	43	< 10	494
24602	201 238	< 0.01	34	960	136	5	7	18	0.02	< 10	< 10	43	< 10	426
24603	201 238	< 0.01	32	920	36	5	6	13	0.02	< 10	< 10	31	< 10	160
24604	201 238	0.01	26	1030	20	5	6	15	0.03	< 10	< 10	36	< 10	150
24605	201 238	< 0.01	27	810	20	5	7	11	0.04	< 10	< 10	40	< 10	122
24606	201 238	0.01	33	850	20	5	8	16	0.05	10	< 10	43	< 10	120
24895	201 238	0.01	18	140	308	10	2	26	0.01	< 10	< 10	15	< 10	232
24896	201 238	0.01	14	260	254	10	2	29	< 0.01	10	< 10	17	< 10	240
24897	201 238	0.01	17	270	144	10	2	26	< 0.01	10	< 10	20	< 10	254
24898	201 238	0.01	15	180	196	10	2	21	< 0.01	< 10	< 10	18	< 10	322
24899	201 238	0.01	16	160	304	10	4	16	< 0.01	10	< 10	18	< 10	386
24900	201 238	0.01	26	310	296	15	7	20	< 0.01	10	< 10	18	< 10	692

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24901	201 238	0.34	< 0.2	5	150	< 0.5	< 2	12.30	< 0.5	13	4	80	5.47	< 10	< 1	0.03	< 10	7.30	5550	< 1
24902	201 238	0.29	< 0.2	20	130	< 0.5	< 2	10.75	< 0.5	23	6	62	4.12	< 10	< 1	0.07	< 10	6.36	3670	< 1
24903	201 238	0.75	< 0.2	20	190	< 0.5	< 2	3.69	< 0.5	45	14	70	7.37	< 10	< 1	0.11	< 10	2.33	5130	< 1
24904	201 238	0.35	< 0.2	< 5	80	< 0.5	< 2	11.55	0.5	26	7	19	2.96	< 10	< 1	0.07	< 10	6.40	3520	< 1
24905	201 238	0.23	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	5	9	3.45	< 10	< 1	0.01	< 10	9.17	4150	< 1
24906	201 238	0.25	< 0.2	15	60	< 0.5	< 2	>15.00	< 0.5	< 1	5	13	4.27	< 10	< 1	0.02	< 10	8.97	5080	1
24907	201 238	0.25	< 0.2	10	70	< 0.5	< 2	14.15	< 0.5	3	8	10	4.04	< 10	< 1	0.04	< 10	8.31	3900	1
24908	201 238	0.87	< 0.2	25	130	< 0.5	< 2	0.13	< 0.5	6	14	10	2.88	< 10	< 1	0.14	20	0.16	565	1
24909	201 238	0.37	< 0.2	20	50	< 0.5	< 2	11.55	< 0.5	5	5	18	5.48	< 10	< 1	0.05	< 10	6.61	4590	< 1
24910	201 238	0.45	< 0.2	40	130	< 0.5	< 2	3.62	< 0.5	22	16	72	7.40	< 10	< 1	0.07	< 10	2.17	5930	2
24911	201 238	0.50	< 0.2	20	400	< 0.5	< 2	4.92	< 0.5	16	11	52	7.96	< 10	2	0.06	< 10	2.66	8090	1
24912	201 238	0.94	2.0	45	110	< 0.5	< 2	0.42	< 0.5	18	16	101	4.73	< 10	< 1	0.13	30	0.31	1920	< 1
24913	201 238	0.75	< 0.2	10	130	< 0.5	< 2	0.36	< 0.5	8	10	36	2.39	< 10	< 1	0.09	10	0.13	325	1
24914	201 238	0.59	2.4	45	100	< 0.5	< 2	4.26	3.0	24	7	151	6.02	< 10	1	0.07	< 10	2.52	3880	< 1
24915	201 238	0.32	< 0.2	5	50	< 0.5	< 2	11.10	0.5	4	8	31	2.78	< 10	< 1	0.04	< 10	6.78	2020	< 1
24916	201 238	0.61	0.6	< 5	90	< 0.5	< 2	4.61	0.5	12	10	32	4.09	< 10	< 1	0.06	< 10	2.81	2760	< 1
24917	201 238	0.32	< 0.2	< 5	60	< 0.5	< 2	7.21	0.5	15	6	40	3.49	< 10	< 1	0.07	< 10	4.39	2010	< 1
24918	201 238	0.16	< 0.2	5	60	< 0.5	< 2	12.15	1.0	6	5	32	2.72	< 10	< 1	0.03	< 10	7.10	1785	< 1
24919	201 238	0.16	< 0.2	< 5	40	< 0.5	< 2	13.75	< 0.5	2	6	16	2.21	< 10	< 1	0.03	< 10	8.17	1585	< 1
24920	201 238	0.56	< 0.2	15	100	< 0.5	< 2	6.23	< 0.5	17	12	34	3.91	< 10	1	0.06	< 10	3.77	2430	1
24921	201 238	1.65	< 0.2	< 5	150	1.0	< 2	0.66	< 0.5	13	23	19	5.08	10	< 1	0.15	30	0.94	2140	< 1
24922	201 238	1.44	0.8	15	190	0.5	< 2	0.45	< 0.5	25	20	61	8.35	10	2	0.23	40	0.91	4420	< 1
24923	201 238	0.74	< 0.2	< 5	120	0.5	< 2	2.63	0.5	12	18	24	4.41	< 10	< 1	0.05	20	1.65	3090	< 1
24924	201 238	0.36	< 0.2	10	130	0.5	< 2	7.69	0.5	14	8	58	3.81	< 10	1	0.04	< 10	4.72	2460	< 1
24925	201 238	0.24	< 0.2	5	50	< 0.5	< 2	11.95	1.0	5	7	33	2.81	< 10	< 1	0.03	< 10	7.21	2220	< 1
24926	201 238	0.29	< 0.2	< 5	50	< 0.5	< 2	10.30	5.0	8	8	46	2.93	< 10	1	0.04	< 10	6.21	2080	< 1
24927	201 238	0.41	2.0	15	40	< 0.5	< 2	7.67	5.5	7	10	51	3.16	< 10	1	0.03	< 10	4.61	2440	1
24928	201 238	0.28	13.8	40	30	< 0.5	< 2	9.10	11.0	21	10	463	5.99	< 10	2	0.03	< 10	5.40	3550	< 1
24929	201 238	0.59	3.4	75	80	< 0.5	< 2	2.68	1.0	31	13	155	6.03	< 10	2	0.06	10	1.70	2670	< 1
24930	201 238	0.25	< 0.2	40	50	< 0.5	< 2	7.68	1.0	15	7	136	4.20	< 10	< 1	0.04	< 10	4.55	2400	< 1
24931	201 238	0.44	< 0.2	50	100	0.5	< 2	6.81	< 0.5	12	7	30	5.97	< 10	2	0.06	< 10	3.93	5260	< 1
24932	201 238	0.24	< 0.2	15	50	< 0.5	< 2	11.90	< 0.5	4	6	16	4.49	< 10	1	0.03	< 10	6.78	4540	< 1
24933	201 238	0.27	< 0.2	5	70	< 0.5	< 2	12.10	< 0.5	3	4	11	4.53	< 10	< 1	0.04	< 10	7.03	4890	< 1
24934	201 238	2.16	< 0.2	5	110	< 0.5	< 2	0.65	< 0.5	42	61	141	10.00	10	< 1	0.29	20	1.62	3870	< 1
24935	201 238	0.28	< 0.2	5	40	< 0.5	< 2	14.10	< 0.5	7	7	59	3.10	< 10	< 1	0.06	< 10	8.28	2760	< 1
24936	201 238	0.30	< 0.2	20	60	< 0.5	< 2	10.70	< 0.5	11	5	13	3.99	< 10	1	0.10	< 10	5.15	2600	< 1
24937	201 238	0.17	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	5	16	2.63	< 10	1	0.01	< 10	10.05	3110	< 1
24938	201 238	0.19	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	5	7	3.01	< 10	< 1	0.01	< 10	9.64	3810	< 1
24939	201 238	0.25	< 0.2	< 5	100	< 0.5	< 2	14.10	< 0.5	< 1	6	32	4.09	< 10	< 1	0.01	< 10	8.40	4840	< 1
24940	201 238	0.17	< 0.2	< 5	1310	< 0.5	< 2	>15.00	< 0.5	3	5	102	4.04	< 10	1	0.01	< 10	9.14	3730	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24901	201 238	0.01	18	260	44	5	5	29	< 0.01	10	< 10	20	< 10	188
24902	201 238	0.01	45	420	12	5	7	38	< 0.01	< 10	< 10	21	< 10	86
24903	201 238	0.01	41	860	28	5	19	23	0.01	10	< 10	48	< 10	144
24904	201 238	0.01	22	740	28	5	6	35	< 0.01	< 10	< 10	16	< 10	180
24905	201 238	0.01	8	< 200	16	5	3	29	< 0.01	< 10	< 10	15	< 10	78
24906	201 238	0.01	12	< 200	48	10	3	35	< 0.01	< 10	< 10	13	< 10	126
24907	201 238	0.01	18	210	74	10	3	31	< 0.01	10	< 10	10	< 10	184
24908	201 238	< 0.01	15	970	34	< 5	< 1	18	0.02	< 10	< 10	37	< 10	58
24909	201 238	0.01	23	720	56	10	5	36	< 0.01	10	< 10	12	< 10	164
24910	201 238	< 0.01	49	700	76	10	9	41	< 0.01	10	< 10	42	< 10	172
24911	201 238	0.01	33	1430	172	10	7	38	< 0.01	10	< 10	25	< 10	128
24912	201 238	0.01	27	1540	190	10	3	20	0.01	10	< 10	25	< 10	188
24913	201 238	< 0.01	13	2370	30	5	< 1	12	< 0.01	< 10	< 10	33	< 10	80
24914	201 238	0.01	28	850	848	20	7	25	0.01	< 10	< 10	22	< 10	2190
24915	201 238	0.01	10	280	330	5	3	19	0.01	10	< 10	14	< 10	360
24916	201 238	0.01	16	600	628	10	5	12	0.02	< 10	< 10	22	< 10	312
24917	201 238	0.01	15	380	160	5	7	15	< 0.01	< 10	< 10	10	< 10	222
24918	201 238	0.01	12	200	72	5	3	38	< 0.01	< 10	< 10	7	< 10	744
24919	201 238	0.01	9	160	48	5	3	32	< 0.01	< 10	< 10	8	< 10	86
24920	201 238	0.01	23	570	36	10	5	16	0.01	10	< 10	20	< 10	118
24921	201 238	0.01	32	770	44	5	8	13	0.04	< 10	< 10	36	< 10	108
24922	201 238	0.01	54	850	286	10	17	12	0.04	10	< 10	32	< 10	204
24923	201 238	0.01	20	790	52	5	6	9	0.01	< 10	< 10	25	< 10	150
24924	201 238	0.01	17	390	436	15	5	14	< 0.01	10	< 10	14	< 10	840
24925	201 238	0.01	11	250	392	10	4	20	< 0.01	< 10	< 10	11	< 10	512
24926	201 238	0.01	12	280	382	5	4	18	< 0.01	< 10	< 10	13	< 10	3210
24927	201 238	0.01	11	570	3550	10	4	13	< 0.01	< 10	< 10	15	< 10	3450
24928	201 238	0.01	24	260	4080	175	4	18	< 0.01	10	< 10	11	< 10	5010
24929	201 238	0.01	33	610	1520	45	6	14	0.02	10	< 10	25	< 10	1350
24930	201 238	0.01	21	330	652	35	4	19	0.01	20	< 10	11	< 10	810
24931	201 238	0.01	27	940	152	10	6	27	< 0.01	< 10	< 10	15	< 10	162
24932	201 238	0.01	19	520	62	10	4	31	< 0.01	< 10	< 10	10	< 10	100
24933	201 238	0.01	15	450	154	5	5	28	< 0.01	< 10	< 10	11	< 10	214
24934	201 238	< 0.01	56	960	98	5	25	23	0.03	20	< 10	143	< 10	332
24935	201 238	0.01	23	250	12	5	5	28	< 0.01	< 10	< 10	17	< 10	70
24936	201 238	0.01	16	660	22	5	7	31	< 0.01	< 10	< 10	16	< 10	90
24937	201 238	0.01	5	< 200	6	5	2	28	< 0.01	< 10	< 10	10	< 10	90
24938	201 238	0.01	5	< 200	10	5	2	24	< 0.01	10	< 10	8	< 10	130
24939	201 238	0.01	9	150	12	5	2	31	< 0.01	< 10	< 10	16	< 10	160
24940	201 238	0.01	13	< 200	66	10	2	39	< 0.01	10	< 10	12	< 10	136

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J 2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDP
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24941	201 238	0.21	< 0.2	15	110	< 0.5	< 2	12.95	< 0.5	18	6	55	3.56	< 10	1	0.03	< 10	7.86	3310	< 1
24942	201 238	0.14	< 0.2	5	250	< 0.5	< 2	>15.00	< 0.5	< 1	3	115	3.59	< 10	< 1	< 0.01	< 10	9.71	3450	< 1
24943	201 238	0.15	< 0.2	25	340	< 0.5	< 2	>15.00	0.5	4	3	100	4.72	< 10	< 1	< 0.01	< 10	9.54	3490	< 1
24944	201 238	0.18	< 0.2	45	740	< 0.5	< 2	13.85	< 0.5	7	1	111	5.02	< 10	< 1	0.01	< 10	8.29	3630	1
24945	201 238	0.26	< 0.2	65	570	< 0.5	< 2	8.65	< 0.5	13	< 1	111	5.51	< 10	1	0.03	< 10	5.10	3730	7
24946	201 238	0.67	< 0.2	35	400	< 0.5	< 2	4.81	< 0.5	13	10	85	5.01	< 10	1	0.05	< 10	2.88	3090	6
24947	201 238	0.43	1.6	35	350	< 0.5	< 2	0.51	0.5	14	4	87	3.95	< 10	< 1	0.09	30	0.15	1305	19
24948	203 238	0.56	0.2	65	840	< 0.5	< 2	4.53	< 0.5	23	74	248	7.22	< 10	< 1	0.18	< 10	2.60	6210	9
24949	201 238	0.33	< 0.2	10	620	< 0.5	< 2	12.15	0.5	11	4	184	6.12	< 10	1	0.02	< 10	7.31	6170	1
24950	201 238	0.21	< 0.2	35	470	< 0.5	< 2	14.30	0.5	6	4	186	4.81	< 10	< 1	< 0.01	< 10	8.47	4340	< 1
24951	201 238	0.13	< 0.2	30	50	< 0.5	< 2	>15.00	< 0.5	< 1	4	69	3.45	< 10	< 1	< 0.01	< 10	9.89	3740	< 1
24952	201 238	0.31	< 0.2	< 5	120	< 0.5	< 2	14.15	1.5	< 1	5	65	4.68	< 10	< 1	0.01	< 10	8.52	5490	< 1
24953	201 238	0.13	< 0.2	< 5	90	< 0.5	< 2	>15.00	< 0.5	< 1	6	66	2.90	< 10	< 1	< 0.01	< 10	10.00	3720	< 1
24954	201 238	0.35	< 0.2	< 5	300	< 0.5	< 2	10.85	1.5	12	7	79	5.34	< 10	< 1	0.05	< 10	6.19	5760	< 1
24955	201 238	0.34	< 0.2	< 5	260	< 0.5	< 2	9.68	0.5	4	3	48	5.46	< 10	1	0.01	< 10	5.71	6490	< 1
24956	201 238	0.09	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	4	14	2.56	< 10	< 1	< 0.01	< 10	10.30	3390	< 1
24957	201 238	0.31	< 0.2	< 5	90	< 0.5	< 2	12.10	0.5	5	8	25	3.90	< 10	1	0.02	< 10	7.11	4110	< 1
24958	201 238	0.16	< 0.2	35	50	< 0.5	< 2	13.35	< 0.5	< 1	3	27	2.91	< 10	< 1	0.02	< 10	7.88	2900	< 1
24959	201 238	0.30	< 0.2	15	80	< 0.5	< 2	9.84	< 0.5	4	4	26	3.60	< 10	1	0.04	< 10	5.88	3510	1
24960	201 238	0.47	< 0.2	30	90	< 0.5	< 2	8.98	< 0.5	12	8	48	4.88	< 10	3	0.07	< 10	5.36	3710	< 1
24961	201 238	0.49	< 0.2	35	80	< 0.5	< 2	7.48	< 0.5	17	10	92	5.16	< 10	1	0.09	< 10	4.64	3870	< 1
24962	201 238	0.36	< 0.2	< 5	100	< 0.5	< 2	9.24	< 0.5	6	8	28	4.03	< 10	1	0.05	< 10	5.67	3500	1
24963	201 238	2.04	1.0	< 5	120	1.5	< 2	0.21	< 0.5	19	22	83	5.96	< 10	1	0.16	20	1.03	1750	< 1
24964	201 238	0.47	1.4	35	100	< 0.5	< 2	4.34	1.0	22	8	65	6.74	< 10	< 1	0.06	< 10	2.52	4460	< 1
24965	201 238	0.25	< 0.2	5	30	< 0.5	< 2	12.85	5.5	2	5	28	3.06	< 10	< 1	0.04	< 10	7.88	2070	< 1
24966	201 238	1.09	28.6	25	70	< 0.5	< 2	0.46	1.0	16	19	62	6.07	10	< 1	0.25	40	0.82	3610	< 1
24967	201 238	0.85	< 0.2	35	90	< 0.5	< 2	6.38	2.5	10	13	32	4.61	< 10	1	0.15	< 10	4.38	1775	< 1
24968	201 238	0.29	< 0.2	< 5	60	< 0.5	< 2	12.00	6.0	3	6	49	2.91	< 10	1	0.02	< 10	7.51	2010	< 1
24969	201 238	0.30	< 0.2	35	70	< 0.5	< 2	12.80	< 0.5	2	6	15	2.84	< 10	< 1	0.06	< 10	8.04	2310	< 1
24970	201 238	0.93	0.2	35	190	< 0.5	< 2	2.48	< 0.5	14	15	37	4.49	< 10	3	0.16	20	1.70	3200	< 1
24971	201 238	0.47	< 0.2	20	110	< 0.5	< 2	9.34	< 0.5	7	6	25	3.92	< 10	4	0.07	< 10	6.03	3060	< 1
24972	201 238	1.05	0.8	15	170	< 0.5	< 2	0.37	2.5	34	18	73	6.76	10	< 1	0.14	40	0.42	3100	< 1
24973	201 238	0.39	< 0.2	< 5	80	< 0.5	< 2	10.05	< 0.5	2	7	13	2.80	< 10	1	0.05	< 10	6.16	2460	< 1
24974	201 238	0.41	< 0.2	35	90	< 0.5	< 2	8.88	0.5	13	10	28	3.41	< 10	< 1	0.06	< 10	5.47	2160	< 1
24975	201 238	0.64	< 0.2	30	110	< 0.5	< 2	4.72	0.5	20	9	35	4.98	< 10	1	0.12	< 10	2.98	3750	< 1
24976	201 238	0.76	2.4	20	80	< 0.5	< 2	3.41	4.0	26	13	57	4.80	< 10	< 1	0.10	10	2.18	2320	< 1
24977	201 238	0.53	4.6	10	30	< 0.5	< 2	8.95	7.5	3	9	37	2.65	< 10	< 1	0.04	< 10	5.71	1225	< 1
24978	201 238	1.18	2.6	25	110	< 0.5	< 2	0.82	0.5	15	16	27	4.54	10	1	0.13	30	0.49	1705	< 1
24979	201 238	1.30	1.2	10	140	< 0.5	< 2	0.43	0.5	19	18	33	5.46	10	< 1	0.19	30	0.48	1875	< 1
24980	201 238	0.46	2.8	35	70	< 0.5	< 2	9.47	4.0	14	12	54	5.22	< 10	< 1	0.06	< 10	5.80	3280	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24941	201	238	0.01	26	160	46	5	5	34	< 0.01	10	< 10	12	< 10	154
24942	201	238	0.01	14	< 200	52	5	2	37	< 0.01	10	< 10	8	< 10	160
24943	201	238	0.01	20	< 200	110	10	2	31	< 0.01	10	< 10	10	< 10	266
24944	201	238	0.01	25	140	88	15	2	31	< 0.01	< 10	< 10	14	< 10	190
24945	201	238	0.01	28	880	248	10	2	21	< 0.01	< 10	< 10	17	< 10	276
24946	201	238	0.01	28	1210	168	10	3	18	0.01	< 10	< 10	25	< 10	284
24947	201	238	< 0.01	51	1580	104	10	5	34	< 0.01	< 10	< 10	11	< 10	644
24948	203	238	0.01	47	890	388	15	5	26	< 0.01	20	< 10	19	< 10	542
24949	201	238	0.01	29	280	422	10	4	31	0.01	< 10	< 10	16	< 10	464
24950	201	238	0.01	20	80	280	10	3	36	< 0.01	< 10	< 10	12	< 10	350
24951	201	238	0.01	18	< 200	76	5	2	55	< 0.01	10	< 10	9	< 10	264
24952	201	238	0.01	16	150	40	5	2	31	0.01	10	< 10	12	< 10	428
24953	201	238	0.01	10	< 200	12	5	2	25	< 0.01	10	< 10	7	< 10	176
24954	201	238	0.01	21	580	66	5	6	38	< 0.01	20	< 10	21	< 10	482
24955	201	238	0.01	11	460	38	10	3	24	< 0.01	10	< 10	17	< 10	344
24956	201	238	0.01	4	< 200	14	5	2	32	< 0.01	< 10	< 10	7	< 10	108
24957	201	238	0.01	17	330	28	10	3	29	< 0.01	20	< 10	14	< 10	256
24958	201	238	0.01	15	140	30	10	3	30	< 0.01	10	< 10	7	< 10	346
24959	201	238	0.01	18	430	34	5	3	25	< 0.01	10	< 10	11	< 10	218
24960	201	238	0.01	23	580	114	5	7	29	< 0.01	10	< 10	22	< 10	154
24961	201	238	0.01	30	710	38	5	8	22	< 0.01	< 10	< 10	27	< 10	124
24962	201	238	0.01	17	610	60	5	4	36	0.01	< 10	< 10	13	< 10	102
24963	201	238	0.01	24	1430	716	15	4	9	0.03	10	< 10	28	< 10	278
24964	201	238	0.01	23	420	1060	15	5	15	0.01	10	< 10	14	< 10	884
24965	201	238	0.01	9	110	322	5	3	25	0.01	< 10	< 10	10	< 10	2420
24966	201	238	0.01	31	640	9630	30	14	6	0.01	10	< 10	17	< 10	964
24967	201	238	0.01	24	450	270	10	7	15	0.02	< 10	< 10	19	< 10	1795
24968	201	238	0.01	8	180	760	5	4	21	0.01	< 10	< 10	12	< 10	4010
24969	201	238	0.01	12	130	54	5	3	21	0.01	< 10	< 10	12	< 10	80
24970	201	238	0.01	24	620	50	5	6	14	0.03	< 10	< 10	30	< 10	110
24971	201	238	0.01	13	330	42	10	4	17	0.01	< 10	< 10	16	< 10	152
24972	201	238	0.01	32	710	110	5	11	14	0.04	10	< 10	32	< 10	2090
24973	201	238	0.01	11	320	32	5	4	21	0.01	10	< 10	15	< 10	154
24974	201	238	0.01	18	540	80	10	5	29	0.02	10	< 10	17	< 10	798
24975	201	238	0.01	24	780	50	5	8	19	0.02	10	< 10	20	< 10	734
24976	201	238	0.01	26	640	3730	5	7	19	0.04	10	< 10	28	< 10	3060
24977	201	238	0.01	9	400	7390	5	3	19	0.02	< 10	< 10	18	< 10	4810
24978	201	238	0.01	21	1050	1015	10	7	15	0.04	< 10	< 10	34	< 10	1220
24979	201	238	0.01	25	960	136	10	9	13	0.04	< 10	< 10	31	< 10	422
24980	201	238	0.01	24	260	862	15	5	29	0.01	10	< 10	14	< 10	2440

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
24981	201 238	0.85	11.4	25	80	< 0.5	< 2	0.41	3.0	15	11	67	6.27	< 10	< 1	0.14	40	0.37	3060	1
24982	201 238	1.24	0.8	20	110	< 0.5	< 2	0.82	< 0.5	15	12	38	4.99	< 10	< 1	0.21	30	0.69	1690	< 1
24983	201 238	0.42	< 0.2	10	100	< 0.5	< 2	9.31	< 0.5	5	7	20	4.65	< 10	2	0.05	< 10	5.68	4470	< 1
24984	201 238	0.76	< 0.2	25	160	< 0.5	< 2	6.75	< 0.5	8	9	36	5.56	< 10	1	0.07	< 10	4.09	5120	1
24985	201 238	0.51	< 0.2	15	100	< 0.5	< 2	10.50	< 0.5	3	6	38	3.85	< 10	1	0.04	< 10	6.53	3650	< 1
24986	201 238	0.26	< 0.2	5	60	< 0.5	< 2	13.60	< 0.5	< 1	1	12	3.47	< 10	3	0.01	< 10	8.34	4350	< 1
24987	201 238	0.50	< 0.2	5	110	< 0.5	< 2	8.60	< 0.5	7	7	26	5.12	< 10	1	0.05	< 10	5.13	5580	1
24988	201 238	0.34	< 0.2	20	100	< 0.5	< 2	13.30	< 0.5	< 1	3	30	3.47	< 10	< 1	0.03	< 10	8.21	3350	1
24989	201 238	0.38	< 0.2	< 5	100	< 0.5	< 2	12.25	< 0.5	< 1	4	20	4.25	< 10	< 1	0.02	< 10	7.33	5270	< 1
24990	201 238	0.38	< 0.2	< 5	140	< 0.5	< 2	9.65	< 0.5	7	6	50	4.97	< 10	< 1	0.04	< 10	5.85	5240	< 1
24991	201 238	0.37	< 0.2	< 5	1210	< 0.5	< 2	11.75	0.5	2	4	174	4.71	< 10	3	0.02	< 10	7.19	5220	3
24992	201 238	0.14	< 0.2	15	140	< 0.5	< 2	>15.00	< 0.5	< 1	< 1	57	3.15	< 10	< 1	< 0.01	< 10	9.33	3760	< 1
24993	201 238	0.16	< 0.2	< 5	1250	< 0.5	< 2	14.65	< 0.5	2	2	51	3.33	< 10	< 1	0.01	< 10	8.78	3660	1
24994	201 238	0.12	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	2	13	3.25	< 10	< 1	< 0.01	< 10	10.40	3990	< 1
24995	201 238	0.21	< 0.2	10	70	< 0.5	< 2	>15.00	< 0.5	< 1	4	53	4.08	< 10	< 1	0.01	< 10	9.55	4610	< 1
24996	201 238	0.51	< 0.2	30	260	< 0.5	< 2	6.83	< 0.5	23	< 1	162	6.45	< 10	1	0.11	< 10	4.19	4050	6
24997	201 238	0.79	1.0	70	2300	< 0.5	< 2	1.98	< 0.5	24	6	184	10.10	10	3	0.08	20	0.84	9140	6
24998	201 238	1.06	1.4	40	860	< 0.5	< 2	0.67	< 0.5	14	16	79	4.96	10	< 1	0.10	20	0.33	1805	12
24999	201 238	0.72	0.4	10	80	< 0.5	< 2	4.53	3.5	11	8	33	3.35	< 10	2	0.08	< 10	2.88	1860	< 1
25000	201 238	0.90	1.0	15	130	< 0.5	< 2	3.02	2.0	11	15	40	4.03	< 10	< 1	0.09	10	1.88	2170	< 1
25001	201 238	1.16	0.4	5	210	0.5	< 2	3.52	3.0	12	19	40	4.56	< 10	1	0.07	10	2.31	2920	< 1
25002	201 238	0.66	< 0.2	5	90	< 0.5	< 2	5.24	1.0	11	13	32	4.72	< 10	< 1	0.09	< 10	3.29	3100	< 1
25003	201 238	1.44	0.8	25	210	< 0.5	< 2	0.82	< 0.5	13	22	41	5.94	10	< 1	0.11	30	0.46	3490	3
25004	201 238	1.65	0.8	30	270	< 0.5	< 2	0.68	< 0.5	17	25	32	5.79	10	< 1	0.10	30	0.43	3710	2
25005	201 238	1.59	0.8	30	240	< 0.5	< 2	0.62	< 0.5	14	24	39	6.33	10	< 1	0.09	30	0.51	3760	3
25006	201 238	1.73	0.6	5	300	< 0.5	< 2	0.82	< 0.5	15	25	30	6.64	10	2	0.09	30	0.58	5040	2
25007	201 238	1.56	0.4	10	250	< 0.5	< 2	0.99	< 0.5	15	26	41	5.79	10	< 1	0.11	30	0.65	3710	2
25008	201 238	1.25	0.4	10	230	< 0.5	< 2	1.57	< 0.5	14	17	63	6.47	10	1	0.06	20	0.96	4440	1
25009	201 238	1.06	< 0.2	5	190	< 0.5	< 2	1.69	< 0.5	13	17	38	5.44	< 10	2	0.07	20	0.86	3080	2
25010	201 238	0.74	< 0.2	10	250	< 0.5	< 2	5.49	< 0.5	13	14	38	4.73	< 10	< 1	0.05	< 10	3.47	3820	1
25011	201 238	0.84	< 0.2	40	230	< 0.5	< 2	3.45	< 0.5	17	17	45	5.47	< 10	3	0.06	< 10	2.08	4080	2
25012	201 238	1.05	< 0.2	35	420	< 0.5	< 2	2.92	< 0.5	14	16	50	7.02	< 10	< 1	0.07	10	1.79	6600	4
25013	201 238	0.24	< 0.2	20	250	< 0.5	< 2	8.55	< 0.5	6	4	53	3.85	< 10	2	0.03	< 10	4.68	4390	3
25014	201 238	1.02	0.4	65	380	< 0.5	< 2	2.04	< 0.5	19	14	69	9.03	10	2	0.08	20	1.12	8080	20
25015	201 238	0.79	< 0.2	5	380	< 0.5	< 2	9.10	< 0.5	7	12	33	6.31	< 10	3	0.05	< 10	5.70	7030	3
25016	201 238	0.56	< 0.2	< 5	170	< 0.5	< 2	12.95	< 0.5	< 1	8	41	5.23	< 10	< 1	0.03	< 10	8.14	6350	1
25017	201 238	0.86	< 0.2	5	250	< 0.5	< 2	7.36	< 0.5	10	14	20	6.11	< 10	1	0.06	< 10	4.58	6630	1
25018	201 238	0.65	< 0.2	30	240	< 0.5	< 2	7.69	< 0.5	17	9	22	9.73	< 10	< 1	0.04	< 10	4.76	8330	7
25019	201 238	0.86	0.2	20	260	< 0.5	< 2	3.11	< 0.5	13	15	52	6.27	< 10	< 1	0.05	10	1.84	5940	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 25-JUL-89
Invoice # : I-8920346
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920346

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
24981	201 238	0.01	23	750	3890	10	8	11	0.03	20	< 10	23	< 10	1820
24982	201 238	0.01	19	1330	162	< 5	8	18	0.02	< 10	< 10	22	< 10	252
24983	201 238	0.01	14	660	36	5	4	27	< 0.01	10	< 10	15	< 10	174
24984	201 238	0.01	22	990	44	10	4	25	0.01	< 10	< 10	23	< 10	244
24985	201 238	0.01	16	490	28	5	3	24	0.01	10	< 10	17	< 10	158
24986	201 238	0.01	5	300	14	5	2	20	< 0.01	< 10	< 10	10	< 10	112
24987	201 238	0.01	19	780	30	5	3	23	0.01	< 10	< 10	15	< 10	186
24988	201 238	0.01	15	290	34	5	3	22	0.01	10	< 10	13	< 10	120
24989	201 238	0.01	9	500	30	5	3	23	0.01	< 10	< 10	14	< 10	152
24990	201 238	0.01	16	630	28	5	7	23	< 0.01	< 10	< 10	22	< 10	174
24991	201 238	0.01	15	300	82	10	3	29	0.01	< 10	< 10	21	< 10	312
24992	201 238	0.01	9	< 200	28	5	2	45	< 0.01	< 10	< 10	9	< 10	134
24993	201 238	0.01	17	< 200	22	5	2	46	< 0.01	< 10	< 10	9	< 10	108
24994	201 238	0.01	10	< 200	26	5	1	33	< 0.01	< 10	< 10	5	< 10	88
24995	201 238	0.01	15	< 200	22	5	2	37	< 0.01	< 10	< 10	8	< 10	120
24996	201 238	0.01	56	1420	90	15	4	83	0.01	< 10	< 10	15	< 10	398
24997	201 238	0.01	54	1640	124	15	4	61	0.01	< 10	< 10	23	< 10	530
24998	201 238	< 0.01	49	1270	50	10	4	18	0.02	< 10	< 10	33	< 10	354
24999	201 238	0.01	18	610	1030	10	5	16	0.02	< 10	< 10	20	< 10	2520
25000	201 238	0.01	22	710	746	5	5	14	0.02	< 10	< 10	27	< 10	2170
25001	201 238	0.01	23	730	886	5	6	16	0.04	< 10	< 10	37	< 10	2330
25002	201 238	0.01	18	830	434	5	6	17	0.01	< 10	< 10	21	< 10	814
25003	201 238	0.01	29	1260	82	5	6	15	0.03	< 10	< 10	41	< 10	240
25004	201 238	< 0.01	30	1020	98	5	6	15	0.02	< 10	< 10	43	< 10	180
25005	201 238	0.01	31	1010	148	5	6	12	0.03	< 10	< 10	46	< 10	242
25006	201 238	0.01	30	1070	108	5	6	14	0.04	< 10	< 10	48	< 10	230
25007	201 238	0.01	31	1020	74	5	6	16	0.04	10	< 10	43	< 10	244
25008	201 238	0.01	28	1350	76	5	5	13	0.02	10	< 10	32	< 10	302
25009	201 238	< 0.01	26	1200	84	5	4	14	0.02	10	< 10	30	< 10	264
25010	201 238	0.01	26	660	70	5	5	18	0.01	10	< 10	22	< 10	226
25011	201 238	0.01	33	830	134	5	5	24	0.01	10	< 10	25	< 10	244
25012	201 238	0.01	32	990	114	5	4	15	0.02	20	< 10	31	< 10	362
25013	201 238	0.01	17	860	32	5	2	26	< 0.01	< 10	< 10	11	< 10	266
25014	201 238	0.01	53	1160	90	10	4	15	0.02	10	< 10	34	< 10	542
25015	201 238	0.01	17	620	36	10	3	15	0.02	10	< 10	26	< 10	226
25016	201 238	0.01	14	330	24	5	2	12	0.01	10	< 10	17	< 10	166
25017	201 238	0.01	24	770	40	5	4	13	0.02	< 10	< 10	23	< 10	190
25018	201 238	0.01	32	500	42	10	5	21	0.01	10	< 10	27	10	192
25019	201 238	0.01	27	570	64	5	5	15	0.01	< 10	< 10	39	< 10	130

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24645	201	238	2.18	0.8	10	150	< 0.5	< 2	0.58	< 0.5	14	32	24	4.44	20	< 1	0.11	20	1.26	875	< 1
T24646	201	238	2.27	0.4	15	200	< 0.5	< 2	0.45	< 0.5	18	34	37	5.23	10	< 1	0.11	20	1.31	2290	2
T24647	201	238	1.55	0.8	5	140	< 0.5	< 2	0.55	< 0.5	11	25	31	4.10	10	< 1	0.11	30	0.82	1445	< 1
T24648	201	238	1.27	1.2	5	140	< 0.5	< 2	0.59	0.5	12	22	81	5.36	10	< 1	0.09	30	0.51	2570	1
T24649	201	238	1.48	0.6	20	150	< 0.5	< 2	0.54	< 0.5	17	22	39	6.31	10	< 1	0.09	30	0.59	3660	1
T24650	201	238	1.01	0.4	15	140	< 0.5	< 2	0.91	< 0.5	16	19	35	5.48	10	< 1	0.08	20	0.47	4120	< 1
T24651	201	238	0.89	0.2	45	170	< 0.5	< 2	0.59	< 0.5	22	10	59	5.98	10	< 1	0.09	40	0.39	5520	< 1
T24652	201	238	0.95	0.8	< 5	100	< 0.5	< 2	0.84	0.5	16	19	31	4.00	10	< 1	0.07	20	0.38	2360	< 1
T24653	201	238	1.08	0.2	20	160	< 0.5	< 2	0.60	< 0.5	24	16	61	6.05	10	< 1	0.06	20	0.47	4590	1
T24654	201	238	0.88	0.6	< 5	100	< 0.5	< 2	0.81	1.5	17	12	59	6.54	< 10	< 1	0.06	20	0.49	4060	2
T24655	201	238	1.15	0.4	35	90	< 0.5	< 2	0.83	< 0.5	21	17	70	6.86	< 10	< 1	0.10	30	0.92	4030	1
T24656	201	238	0.84	1.0	30	90	< 0.5	< 2	1.29	1.5	19	10	57	5.31	< 10	< 1	0.07	20	0.83	3370	2
T24657	201	238	0.78	2.0	10	60	< 0.5	< 2	1.59	0.5	13	11	50	4.32	< 10	< 1	0.07	20	1.00	1685	< 1
T24658	201	238	0.84	7.2	5	30	< 0.5	< 2	1.14	6.5	7	15	61	4.00	< 10	< 1	0.07	20	0.88	705	< 1
T24659	201	238	1.09	10.2	15	70	< 0.5	< 2	1.98	4.0	18	19	46	3.92	< 10	< 1	0.08	20	1.56	1320	< 1
T24660	201	238	0.81	4.6	35	60	< 0.5	< 2	4.06	1.5	16	16	36	3.13	< 10	< 1	0.06	< 10	2.84	1320	< 1
T24661	201	238	0.99	< 0.2	20	60	< 0.5	< 2	5.18	4.5	16	17	44	6.31	< 10	< 1	0.09	< 10	3.77	3390	< 1
T24662	201	238	1.29	< 0.2	35	60	< 0.5	< 2	7.35	5.0	14	25	47	6.15	< 10	< 1	0.10	< 10	5.48	3700	< 1
T24663	201	238	0.44	12.8	65	20	< 0.5	< 2	11.25	36.0	7	9	126	3.34	< 10	< 1	0.05	< 10	7.42	2160	< 1
T24664	201	238	0.47	4.2	70	20	< 0.5	< 2	10.85	16.5	7	7	61	3.49	< 10	< 1	0.05	< 10	7.27	2110	< 1
T24665	201	238	0.26	< 0.2	35	20	< 0.5	< 2	13.35	10.5	< 1	5	34	2.47	< 10	< 1	0.03	< 10	8.51	1715	< 1
T24666	201	238	0.24	30.6	105	10	< 0.5	< 2	12.75	16.0	7	6	119	3.66	< 10	< 1	0.02	< 10	7.95	2740	1
T24697	201	238	0.96	1.0	85	110	< 0.5	2	2.12	1.0	20	11	47	5.52	< 10	< 1	0.07	10	1.57	2240	4
T24698	201	238	0.34	< 0.2	180	30	< 0.5	< 2	6.62	6.0	22	6	32	5.39	< 10	< 1	0.04	< 10	4.17	1985	3
T24699	201	238	0.31	< 0.2	145	30	< 0.5	< 2	6.76	6.5	21	7	32	5.17	< 10	< 1	0.05	< 10	4.17	1930	5
T24700	201	238	0.61	< 0.2	80	70	< 0.5	< 2	7.08	0.5	19	9	34	5.52	< 10	< 1	0.07	< 10	4.55	2790	1
T24701	201	238	0.76	< 0.2	105	100	< 0.5	2	3.06	< 0.5	19	11	33	5.51	< 10	< 1	0.07	10	1.96	2850	2
T24702	201	238	0.95	< 0.2	50	110	< 0.5	< 2	5.08	< 0.5	18	16	43	5.74	< 10	< 1	0.07	< 10	3.20	3400	1
T24703	201	238	1.06	< 0.2	20	100	< 0.5	< 2	4.01	0.5	21	18	55	4.58	< 10	< 1	0.11	< 10	2.72	2670	< 1
T24704	201	238	0.93	< 0.2	5	70	< 0.5	4	1.00	< 0.5	26	22	68	5.39	< 10	< 1	0.09	10	0.72	1835	1
T24705	201	238	0.99	< 0.2	45	90	< 0.5	< 2	4.53	< 0.5	15	16	32	3.70	< 10	< 1	0.09	< 10	3.10	1705	1
T24706	201	238	1.33	< 0.2	60	120	< 0.5	4	0.71	< 0.5	14	19	34	4.95	10	< 1	0.09	20	0.55	2100	< 1
T24707	201	238	1.03	< 0.2	25	120	< 0.5	2	1.77	< 0.5	28	14	65	4.87	10	< 1	0.09	10	1.21	2400	1
T24708	201	238	0.67	0.4	40	100	< 0.5	< 2	7.16	< 0.5	22	12	26	5.37	< 10	< 1	0.06	< 10	4.53	3310	1
T24709	201	238	1.06	< 0.2	40	140	< 0.5	2	0.78	< 0.5	12	12	37	4.84	10	< 1	0.08	20	0.42	3510	1
T24710	201	238	1.11	< 0.2	50	140	< 0.5	4	2.35	< 0.5	17	15	17	4.30	< 10	< 1	0.06	20	1.58	2220	1
T24711	201	238	1.29	< 0.2	65	150	< 0.5	4	1.76	< 0.5	18	22	20	5.67	< 10	< 1	0.06	20	1.25	3000	1
T24712	201	238	0.87	0.4	45	100	< 0.5	< 2	3.66	< 0.5	17	14	33	4.51	< 10	< 1	0.06	10	2.44	2120	1
T24713	201	238	0.52	0.8	90	90	< 0.5	< 2	7.14	< 0.5	23	8	29	6.20	< 10	< 1	0.05	< 10	4.14	2500	3
T24714	201	238	1.22	< 0.2	50	160	< 0.5	< 2	1.48	< 0.5	18	17	32	5.06	10	< 1	0.07	20	0.86	3090	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

'RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDF
Comments:

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24645	201	238	0.01	23	1200	20	5	7	15	0.13	20	< 10	90	< 10	206
T24646	201	238	0.01	28	1090	32	< 5	8	16	0.11	< 10	< 10	81	< 10	216
T24647	201	238	0.01	22	990	18	5	7	15	0.07	10	< 10	54	< 10	130
T24648	201	238	0.01	24	990	34	< 5	8	14	0.05	10	< 10	43	< 10	114
T24649	201	238	0.01	26	980	28	< 5	10	13	0.04	20	< 10	51	< 10	128
T24650	201	238	0.01	27	1060	14	5	7	17	0.03	20	< 10	37	< 10	104
T24651	201	238	0.01	34	1080	48	5	8	19	0.03	20	< 10	27	< 10	110
T24652	201	238	< 0.01	14	1220	58	< 5	4	20	0.01	30	< 10	25	< 10	164
T24653	201	238	0.01	32	1000	50	5	7	16	0.02	10	< 10	35	< 10	428
T24654	201	238	< 0.01	27	1010	106	< 5	8	15	0.01	10	< 10	29	< 10	790
T24655	201	238	< 0.01	31	960	70	5	8	16	0.01	30	< 10	32	< 10	334
T24656	201	238	0.01	26	900	542	5	6	16	0.02	< 10	< 10	23	< 10	1890
T24657	201	238	0.01	20	930	750	5	5	17	0.02	10	< 10	24	< 10	1970
T24658	201	238	0.01	22	610	3770	5	6	7	0.02	10	< 10	25	< 10	5290
T24659	201	238	0.01	30	650	4140	15	6	13	0.04	10	< 10	37	< 10	3620
T24660	201	238	0.01	25	600	3800	10	5	14	0.04	< 10	< 10	29	< 10	2550
T24661	201	238	0.01	29	760	1035	5	12	15	0.01	20	< 10	34	< 10	3310
T24662	201	238	0.01	41	490	1075	10	18	17	0.01	20	< 10	52	< 10	3360
T24663	201	238	0.01	19	240	>10000	15	4	25	0.01	20	< 10	17	< 10	>10000
T24664	201	238	0.01	18	200	8610	15	4	15	0.01	20	< 10	14	< 10	>10000
T24665	201	238	0.01	12	80	4740	10	4	17	< 0.01	10	< 10	11	< 10	5050
T24666	201	238	0.01	16	90	>10000	50	3	26	< 0.01	10	< 10	13	10	9670
T24697	201	238	< 0.01	45	530	230	10	6	10	0.02	< 10	< 10	29	10	1880
T24698	201	238	< 0.01	59	220	228	15	4	38	< 0.01	< 10	< 10	12	10	3780
T24699	201	238	< 0.01	43	240	126	15	4	44	< 0.01	20	10	10	< 10	3780
T24700	201	238	0.01	35	450	158	15	6	47	0.01	10	< 10	25	10	876
T24701	201	238	0.01	41	520	66	15	5	20	0.01	20	< 10	20	< 10	338
T24702	201	238	0.01	30	630	56	10	9	46	0.01	20	< 10	40	10	424
T24703	201	238	0.01	32	720	26	5	8	22	0.01	10	< 10	33	< 10	168
T24704	201	238	< 0.01	37	660	32	< 5	11	15	0.01	10	< 10	38	< 10	164
T24705	201	238	0.01	23	550	30	5	5	20	0.03	10	< 10	27	< 10	296
T24706	201	238	< 0.01	25	770	30	10	6	11	0.03	< 10	< 10	36	< 10	266
T24707	201	238	< 0.01	25	760	24	5	6	12	0.02	< 10	< 10	28	< 10	248
T24708	201	238	0.01	45	380	34	10	6	26	0.01	20	< 10	22	10	144
T24709	201	238	< 0.01	22	820	20	10	5	11	0.02	< 10	< 10	29	< 10	184
T24710	201	238	0.01	26	530	32	10	5	18	0.03	10	< 10	35	< 10	146
T24711	201	238	0.01	27	610	38	10	4	14	0.03	20	< 10	41	< 10	206
T24712	201	238	0.01	25	590	58	5	4	16	0.02	10	< 10	25	< 10	284
T24713	201	238	0.01	36	350	94	10	4	22	0.01	10	< 10	15	< 10	396
T24714	201	238	0.01	27	740	38	5	6	13	0.02	10	< 10	36	< 10	210

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: .CHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page N. : 2-A
Tot. Pages: 5
Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24715	201	238	0.49	0.4	30	90	< 0.5	< 2	7.50	< 0.5	21	5	38	3.56	< 10	2	0.05	< 10	4.55	1340	1
T24716	201	238	1.42	< 0.2	35	190	< 0.5	< 2	1.94	< 0.5	22	29	76	6.15	10	< 1	0.10	20	1.38	3660	3
T24717	201	238	0.58	< 0.2	15	60	< 0.5	< 2	13.40	< 0.5	< 1	9	46	3.56	< 10	< 1	0.05	< 10	8.05	3360	1
T24718	201	238	0.38	< 0.2	< 5	40	< 0.5	< 2	14.95	< 0.5	< 1	9	34	2.54	< 10	1	0.04	< 10	8.81	2630	< 1
T24719	201	238	0.40	< 0.2	5	60	< 0.5	< 2	12.80	< 0.5	< 1	5	41	3.38	< 10	< 1	0.04	< 10	7.45	3540	< 1
T24720	201	238	1.17	< 0.2	35	180	0.5	< 2	5.97	1.5	16	17	80	6.33	< 10	2	0.12	< 10	3.81	6330	1
T24721	201	238	0.36	0.4	5	80	< 0.5	< 2	13.55	6.0	1	4	77	4.35	< 10	< 1	0.03	< 10	7.99	4520	< 1
T24722	201	238	0.27	< 0.2	20	290	< 0.5	< 2	>15.00	7.0	< 1	3	139	3.63	< 10	< 1	0.01	< 10	9.39	4280	< 1
T24723	201	238	0.73	< 0.2	20	120	< 0.5	< 2	10.80	< 0.5	3	12	240	3.62	< 10	< 1	0.05	< 10	6.71	3030	< 1
T24724	201	238	0.57	< 0.2	10	110	< 0.5	< 2	13.70	0.5	< 1	9	228	4.77	< 10	1	0.02	< 10	8.28	5830	< 1
T24725	201	238	0.19	0.4	< 5	40	< 0.5	< 2	>15.00	2.5	< 1	< 1	31	2.71	< 10	< 1	0.01	< 10	10.35	2850	2
T24726	201	238	0.28	< 0.2	25	60	< 0.5	< 2	>15.00	< 0.5	< 1	1	26	3.29	< 10	1	0.01	< 10	9.95	3560	1
T24727	201	238	0.25	< 0.2	5	40	< 0.5	< 2	>15.00	0.5	< 1	4	56	3.13	< 10	< 1	0.01	< 10	10.25	3440	< 1
T24728	201	238	1.00	< 0.2	20	160	< 0.5	< 2	8.97	< 0.5	7	12	112	8.94	< 10	< 1	0.06	< 10	5.58	8190	< 1
T24729	201	238	1.03	0.2	50	220	< 0.5	< 2	7.39	< 0.5	16	17	62	7.82	< 10	< 1	0.05	< 10	4.54	6540	3
T24730	201	238	1.24	< 0.2	90	220	< 0.5	< 2	5.21	< 0.5	24	21	65	8.84	< 10	< 1	0.06	< 10	3.38	7090	3
T24731	201	238	1.97	< 0.2	15	140	< 0.5	< 2	0.13	< 0.5	11	26	26	5.16	10	< 1	0.09	20	0.45	1400	2
T24732	201	238	1.70	< 0.2	20	180	< 0.5	< 2	0.52	< 0.5	12	25	17	4.61	10	< 1	0.09	20	0.60	2310	1
T24733	201	238	1.89	< 0.2	15	260	< 0.5	< 2	0.41	< 0.5	9	29	12	3.38	10	< 1	0.11	20	0.51	790	< 1
T24734	201	238	2.01	< 0.2	25	210	< 0.5	< 2	0.38	< 0.5	12	29	14	4.21	10	< 1	0.10	20	0.54	1220	1
T24735	201	238	2.11	< 0.2	45	220	< 0.5	< 2	0.38	< 0.5	14	31	19	5.03	10	1	0.11	20	0.67	1985	1
T24736	201	238	2.11	< 0.2	35	190	< 0.5	< 2	0.19	< 0.5	12	25	38	4.65	< 10	< 1	0.12	30	0.71	1585	1
T24737	201	238	1.55	< 0.2	10	220	< 0.5	< 2	0.59	< 0.5	13	25	19	4.78	< 10	< 1	0.07	20	0.60	1810	< 1
T24738	201	238	1.21	< 0.2	20	110	< 0.5	< 2	2.32	0.5	19	23	55	4.25	< 10	< 1	0.12	20	1.85	1845	1
T24739	201	238	1.25	0.6	65	210	< 0.5	< 2	0.95	< 0.5	18	21	41	5.85	< 10	< 1	0.11	20	0.68	2590	2
T24740	201	238	1.02	0.6	60	150	< 0.5	< 2	1.13	< 0.5	18	16	31	6.07	< 10	1	0.07	20	0.58	2790	2
T24741	201	238	0.91	0.6	90	130	< 0.5	< 2	4.35	< 0.5	26	20	28	6.71	< 10	< 1	0.06	< 10	2.74	3230	2
T24742	201	238	1.09	< 0.2	30	130	< 0.5	< 2	6.31	< 0.5	15	18	19	4.71	< 10	2	0.07	< 10	4.15	2750	1
T24743	201	238	0.35	< 0.2	5	80	< 0.5	< 2	9.00	< 0.5	4	5	14	4.30	< 10	< 1	0.04	< 10	5.42	3470	< 1
T24744	201	238	0.76	0.4	60	280	< 0.5	< 2	1.39	< 0.5	19	12	41	7.27	< 10	< 1	0.09	20	0.42	2600	1
T24745	201	238	0.44	2.0	85	90	< 0.5	< 2	4.75	5.5	25	2	187	6.18	< 10	< 1	0.07	< 10	2.80	2410	4
T24746	201	238	0.28	1.4	65	30	< 0.5	< 2	8.06	3.0	13	4	34	4.08	< 10	< 1	0.05	< 10	4.94	1850	< 1
T24747	201	238	0.65	0.6	50	180	< 0.5	< 2	3.43	< 0.5	18	7	55	6.15	< 10	1	0.09	10	2.06	3580	1
T24748	201	238	0.47	2.0	110	50	< 0.5	< 2	8.79	6.0	16	5	46	5.22	< 10	< 1	0.06	< 10	5.58	2280	4
T24749	201	238	0.30	3.4	325	50	< 0.5	< 2	9.94	10.5	30	2	44	7.32	< 10	3	0.02	< 10	6.36	1470	2
T24750	201	238	0.35	0.4	35	60	< 0.5	< 2	9.99	1.5	7	6	30	3.59	< 10	< 1	0.07	< 10	6.10	2250	1
T24751	201	238	0.65	< 0.2	60	210	< 0.5	< 2	4.26	< 0.5	17	8	55	5.53	< 10	< 1	0.09	< 10	2.50	3090	1
T24752	201	238	0.28	< 0.2	160	30	< 0.5	< 2	7.82	< 0.5	23	3	26	5.47	< 10	1	0.04	< 10	4.83	2030	3
T24753	201	238	0.58	< 0.2	55	460	< 0.5	< 2	2.71	< 0.5	28	8	53	7.16	< 10	< 1	0.10	10	1.06	4140	2
T24754	201	238	0.23	< 0.2	25	70	< 0.5	< 2	10.75	< 0.5	5	5	19	3.52	< 10	< 1	0.03	< 10	6.48	2260	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: CHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24715	201	238	0.01	30	370	32	10	4	27	0.01	< 10	< 10	14	< 10	180
T24716	201	238	0.01	34	980	52	5	6	17	0.02	30	< 10	36	< 10	258
T24717	201	238	0.01	12	110	20	5	3	18	0.01	< 10	< 10	13	< 10	136
T24718	201	238	0.01	8	40	22	< 5	2	21	0.01	20	< 10	9	< 10	142
T24719	201	238	0.01	12	210	46	5	2	42	< 0.01	10	< 10	10	< 10	244
T24720	201	238	0.01	34	720	96	10	5	24	0.02	20	< 10	25	< 10	740
T24721	201	238	0.01	17	150	182	5	2	46	< 0.01	< 10	< 10	9	< 10	1220
T24722	201	238	0.01	13	20	96	< 5	2	31	< 0.01	< 10	< 10	7	< 10	1825
T24723	201	238	0.01	20	290	16	5	3	20	0.04	< 10	< 10	24	< 10	206
T24724	201	238	0.01	12	200	44	5	2	15	0.01	< 10	< 10	15	< 10	280
T24725	201	238	0.01	9	< 10	218	5	1	18	< 0.01	< 10	< 10	5	< 10	490
T24726	201	238	0.01	9	20	60	5	2	16	< 0.01	< 10	< 10	8	< 10	242
T24727	201	238	0.01	5	< 10	50	5	2	21	< 0.01	< 10	< 10	6	< 10	210
T24728	201	238	0.01	22	500	16	10	5	17	0.02	20	< 10	22	< 10	196
T24729	201	238	0.01	31	770	26	10	5	23	0.02	10	< 10	34	< 10	198
T24730	201	238	0.01	36	720	32	10	6	15	0.03	20	< 10	40	< 10	226
T24731	201	238	< 0.01	20	630	28	5	3	9	0.04	< 10	< 10	57	< 10	110
T24732	201	238	0.01	18	880	32	< 5	4	12	0.03	10	< 10	40	< 10	146
T24733	201	238	0.01	14	750	20	5	3	16	0.05	< 10	< 10	62	< 10	102
T24734	201	238	0.01	19	540	34	5	4	13	0.05	10	< 10	57	< 10	266
T24735	201	238	0.01	23	740	60	5	5	14	0.04	10	< 10	54	< 10	136
T24736	201	238	0.01	27	730	34	5	5	11	0.03	< 10	< 10	46	< 10	178
T24737	201	238	< 0.01	17	1160	36	< 5	4	10	0.02	10	< 10	37	< 10	166
T24738	201	238	0.01	31	790	36	5	5	16	0.02	10	< 10	26	< 10	274
T24739	201	238	0.01	35	800	42	5	7	21	0.03	10	< 10	34	< 10	218
T24740	201	238	0.01	32	760	30	10	8	20	0.02	< 10	< 10	34	< 10	254
T24741	201	238	0.01	38	550	46	10	8	33	0.01	10	< 10	35	< 10	212
T24742	201	238	0.01	27	440	30	10	6	27	0.03	< 10	< 10	34	< 10	226
T24743	201	238	0.01	13	440	24	5	5	72	< 0.01	10	< 10	9	< 10	100
T24744	201	238	< 0.01	40	1340	50	10	8	29	0.01	10	< 10	19	< 10	176
T24745	201	238	0.01	38	510	74	10	6	50	< 0.01	< 10	< 10	10	< 10	2170
T24746	201	238	< 0.01	27	170	392	10	5	43	< 0.01	10	< 10	13	< 10	1830
T24747	201	238	< 0.01	44	810	56	5	6	18	< 0.01	10	< 10	17	< 10	308
T24748	201	238	0.01	41	270	724	10	5	19	< 0.01	10	< 10	16	< 10	3000
T24749	201	238	0.01	100	60	284	15	4	19	< 0.01	10	< 10	11	< 10	6800
T24750	201	238	0.01	25	320	182	5	5	38	< 0.01	10	< 10	11	< 10	938
T24751	201	238	0.01	38	830	60	5	6	23	< 0.01	20	< 10	14	< 10	404
T24752	201	238	0.01	47	170	66	15	4	31	< 0.01	10	< 10	8	< 10	1000
T24753	201	238	< 0.01	57	1040	62	10	7	47	< 0.01	10	< 10	14	< 10	160
T24754	201	238	0.01	22	310	26	5	4	106	< 0.01	< 10	< 10	6	< 10	72

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24755	201	238	1.04	0.2	15	90	< 0.5	< 2	1.13	< 0.5	25	21	52	6.89	< 10	< 1	0.07	10	0.58	3060	1
T24756	201	238	0.67	< 0.2	50	120	< 0.5	< 2	5.14	< 0.5	25	14	26	6.11	< 10	< 1	0.08	< 10	3.18	2780	1
T24757	201	238	0.47	< 0.2	40	210	< 0.5	< 2	5.94	< 0.5	10	19	16	7.16	< 10	1	0.02	< 10	3.24	5670	1
T24758	201	238	1.11	< 0.2	45	190	< 0.5	< 2	2.98	< 0.5	17	10	53	4.50	< 10	< 1	0.08	10	2.19	2490	1
T24759	201	238	1.36	0.4	35	230	< 0.5	< 2	0.55	< 0.5	17	20	50	5.27	< 10	1	0.08	20	0.63	2270	1
T24760	201	238	1.91	< 0.2	20	170	< 0.5	< 2	0.27	< 0.5	6	25	13	3.95	< 10	< 1	0.06	10	0.48	835	1
T24761	201	238	2.01	0.4	50	260	< 0.5	< 2	0.52	< 0.5	17	25	85	6.72	< 10	< 1	0.12	30	0.73	3700	3
T24762	201	238	1.54	0.4	30	420	< 0.5	< 2	0.75	< 0.5	15	16	60	5.13	< 10	1	0.11	20	0.71	2120	1
T24763	201	238	1.46	0.2	30	220	< 0.5	< 2	1.04	< 0.5	14	18	41	5.39	< 10	< 1	0.08	20	0.57	3000	3
T24764	201	238	1.19	0.4	30	140	< 0.5	< 2	0.74	< 0.5	18	15	38	5.13	< 10	< 1	0.09	20	0.41	1995	2
T24765	201	238	1.61	< 0.2	25	190	< 0.5	< 2	1.33	< 0.5	12	26	36	5.50	< 10	< 1	0.06	20	0.89	2790	1
T24766	201	238	1.27	< 0.2	25	220	< 0.5	< 2	1.69	< 0.5	16	14	46	8.50	< 10	1	0.07	20	1.06	6070	3
T24767	201	238	0.44	< 0.2	30	90	< 0.5	< 2	13.35	< 0.5	4	6	16	5.69	< 10	1	0.02	< 10	8.40	4720	1
T24768	201	238	0.24	< 0.2	< 5	50	< 0.5	< 2	>15.00	< 0.5	< 1	1	7	4.55	< 10	< 1	< 0.01	< 10	10.35	4010	< 1
T24769	201	238	1.48	1.2	40	630	< 0.5	< 2	1.17	< 0.5	13	18	75	4.75	10	1	0.13	20	0.62	1210	4
T24770	201	238	1.97	0.4	30	170	< 0.5	< 2	1.46	< 0.5	12	31	32	5.93	10	2	0.07	30	1.29	3570	< 1
T24771	201	238	0.46	< 0.2	< 5	100	< 0.5	< 2	13.80	< 0.5	< 1	8	10	3.71	< 10	< 1	0.02	< 10	8.75	4010	< 1
T24772	201	238	0.44	< 0.2	30	100	< 0.5	< 2	13.70	< 0.5	< 1	5	13	4.83	< 10	2	0.02	< 10	8.61	4430	1
T24773	201	238	0.41	< 0.2	15	60	< 0.5	< 2	13.00	< 0.5	< 1	1	31	3.74	< 10	< 1	0.02	< 10	8.16	3740	< 1
T24775	201	238	0.47	< 0.2	< 5	80	< 0.5	< 2	14.65	< 0.5	< 1	5	91	3.06	< 10	< 1	0.02	< 10	9.40	2760	< 1
T24776	201	238	1.02	1.6	55	220	< 0.5	< 2	1.80	< 0.5	16	9	141	7.07	< 10	1	0.10	20	0.72	3240	10
T24777	201	238	0.70	0.8	25	1060	< 0.5	< 2	1.80	5.5	17	8	112	6.92	10	< 1	0.13	30	0.84	4130	5
T24778	201	238	0.54	< 0.2	65	110	< 0.5	< 2	10.00	< 0.5	6	1	31	9.40	< 10	< 1	0.04	< 10	6.42	5890	8
T24779	201	238	0.81	< 0.2	5	140	< 0.5	< 2	8.91	< 0.5	5	9	31	6.13	< 10	< 1	0.04	< 10	5.70	5280	1
T24780	201	238	1.05	< 0.2	15	180	< 0.5	< 2	1.52	< 0.5	10	11	24	4.85	< 10	< 1	0.05	20	0.91	2610	< 1
T24781	201	238	0.47	< 0.2	40	80	< 0.5	< 2	8.70	< 0.5	5	7	34	3.92	< 10	< 1	0.06	< 10	5.48	3020	< 1
T24782	201	238	1.20	< 0.2	15	490	< 0.5	< 2	1.00	< 0.5	14	13	56	3.96	< 10	< 1	0.11	20	0.55	1465	1
T24783	201	238	1.52	0.2	25	220	< 0.5	< 2	0.34	< 0.5	17	22	46	4.88	< 10	< 1	0.09	20	0.58	2140	1
T24784	201	238	1.46	< 0.2	15	170	< 0.5	< 2	0.21	< 0.5	12	16	53	4.18	< 10	< 1	0.09	20	0.45	1580	1
T24785	201	238	1.36	< 0.2	20	230	< 0.5	< 2	0.47	< 0.5	5	16	15	2.73	< 10	< 1	0.07	20	0.38	430	1
T24786	201	238	1.60	0.4	25	210	< 0.5	< 2	0.23	< 0.5	14	24	40	3.80	< 10	< 1	0.09	30	0.59	1480	< 1
T24787	201	238	1.26	< 0.2	40	150	< 0.5	< 2	3.86	< 0.5	15	17	40	5.95	< 10	1	0.08	< 10	2.64	3780	1
T24788	201	238	0.42	< 0.2	5	90	< 0.5	< 2	9.03	0.5	5	9	17	4.13	< 10	< 1	0.05	< 10	5.73	3600	< 1
T24789	201	238	0.51	< 0.2	20	120	< 0.5	< 2	7.98	0.5	7	9	18	4.75	< 10	< 1	0.06	< 10	5.11	4050	< 1
T24790	201	238	0.23	< 0.2	20	100	< 0.5	< 2	12.20	< 0.5	< 1	8	12	3.27	< 10	< 1	0.04	< 10	7.53	2890	< 1
T24791	201	238	0.77	0.6	20	280	< 0.5	< 2	0.96	< 0.5	18	10	63	5.30	< 10	1	0.14	30	0.56	2640	1
T24792	201	238	1.12	< 0.2	35	430	< 0.5	< 2	4.50	< 0.5	17	9	40	6.57	< 10	3	0.10	< 10	3.36	4580	< 1
T24793	201	238	0.78	< 0.2	50	150	< 0.5	< 2	5.12	< 0.5	20	6	18	7.44	< 10	1	0.15	< 10	3.42	4680	< 1
T24794	201	238	0.87	0.4	55	240	< 0.5	< 2	2.51	< 0.5	26	10	105	6.97	< 10	< 1	0.17	20	1.58	3120	1
T24795	201	238	0.63	< 0.2	225	80	< 0.5	< 2	8.69	16.0	27	7	77	7.18	< 10	2	0.04	< 10	6.07	2470	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920070
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24755	201 238	0.01	36	940	52	5	13	19	< 0.01	< 10	< 10	34	< 10	238
T24756	201 238	0.01	42	940	32	10	11	58	0.01	10	< 10	36	< 10	252
T24757	201 238	0.01	25	840	22	10	7	71	< 0.01	< 10	< 10	63	< 10	240
T24758	201 238	0.01	29	610	30	5	5	19	0.03	< 10	< 10	28	< 10	154
T24759	201 238	< 0.01	31	710	30	5	6	15	0.02	20	< 10	33	< 10	170
T24760	201 238	< 0.01	16	800	16	5	1	11	0.03	10	< 10	49	< 10	84
T24761	201 238	< 0.01	36	910	32	5	7	14	0.02	20	< 10	41	< 10	164
T24762	201 238	0.01	27	930	34	5	6	16	0.02	< 10	< 10	33	< 10	166
T24763	201 238	0.01	28	1260	28	5	4	19	0.02	< 10	< 10	32	< 10	164
T24764	201 238	< 0.01	25	870	48	5	5	15	0.02	< 10	< 10	32	< 10	182
T24765	201 238	0.01	27	1130	20	5	5	15	0.03	< 10	< 10	42	< 10	126
T24766	201 238	0.01	34	950	54	5	6	13	0.02	< 10	< 10	32	< 10	446
T24767	201 238	0.01	20	170	14	5	3	21	0.01	30	< 10	14	< 10	122
T24768	201 238	0.01	9	< 10	14	< 5	2	23	< 0.01	< 10	< 10	8	< 10	80
T24769	201 238	0.01	32	1170	28	5	5	36	0.02	< 10	< 10	37	< 10	140
T24770	201 238	0.01	26	800	14	5	5	16	0.05	20	< 10	51	< 10	152
T24771	201 238	0.01	9	160	8	5	2	12	0.01	< 10	< 10	10	< 10	120
T24772	201 238	0.01	14	150	20	15	2	15	< 0.01	10	< 10	13	< 10	124
T24773	201 238	0.01	11	170	12	5	2	16	0.01	10	< 10	9	< 10	156
T24775	201 238	0.01	9	< 10	16	5	3	15	0.01	10	< 10	11	< 10	118
T24776	201 238	0.01	33	1760	84	10	8	37	0.01	10	< 10	32	< 10	410
T24777	201 238	0.01	32	1170	414	5	6	28	< 0.01	10	< 10	23	< 10	1685
T24778	201 238	0.01	33	160	32	10	3	22	< 0.01	10	< 10	21	< 10	74
T24779	201 238	0.01	16	620	18	10	3	22	0.01	20	< 10	28	< 10	168
T24780	201 238	< 0.01	17	980	22	< 5	5	14	0.01	< 10	< 10	25	< 10	110
T24781	201 238	0.01	16	440	18	5	5	18	0.01	20	< 10	11	< 10	64
T24782	201 238	< 0.01	22	830	32	5	4	15	0.01	10	< 10	24	< 10	136
T24783	201 238	< 0.01	28	590	34	5	6	12	0.03	20	< 10	34	< 10	142
T24784	201 238	< 0.01	24	820	26	5	3	9	0.01	10	< 10	29	< 10	114
T24785	201 238	< 0.01	12	890	14	5	2	12	0.02	10	< 10	35	< 10	68
T24786	201 238	< 0.01	26	460	20	5	4	11	0.03	< 10	< 10	35	< 10	114
T24787	201 238	0.01	23	750	24	5	5	15	0.02	10	< 10	32	< 10	124
T24788	201 238	0.01	15	320	34	5	4	36	< 0.01	10	< 10	10	< 10	728
T24789	201 238	0.01	17	460	28	5	4	37	< 0.01	10	< 10	11	< 10	592
T24790	201 238	0.01	11	240	10	5	4	47	< 0.01	< 10	< 10	7	< 10	78
T24791	201 238	< 0.01	27	1000	28	5	6	33	0.01	< 10	< 10	15	< 10	122
T24792	201 238	0.01	40	1040	24	10	7	30	0.01	< 10	< 10	15	< 10	248
T24793	201 238	0.01	36	420	36	10	11	47	0.01	< 10	< 10	13	< 10	96
T24794	201 238	0.01	60	960	86	10	7	24	0.01	20	< 10	14	< 10	246
T24795	201 238	0.01	80	100	256	15	4	20	< 0.01	10	10	14	< 10	9420

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
5125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24796	201 238	0.40	< 0.2	40	150	< 0.5	< 2	11.85	13.0	7	7	95	4.04	< 10	1	0.04	< 10	7.31	2830	< 1
T25020	201 238	0.21	< 0.2	< 5	190	< 0.5	< 2	>15.00	< 0.5	< 1	7	12	3.60	< 10	< 1	0.01	< 10	9.58	3970	< 1
T25021	201 238	0.38	< 0.2	< 5	190	< 0.5	< 2	12.55	< 0.5	< 1	4	18	4.64	< 10	1	0.02	< 10	7.81	5460	< 1
T25022	201 238	0.27	< 0.2	< 5	60	< 0.5	< 2	>15.00	< 0.5	< 1	< 1	8	3.81	< 10	< 1	< 0.01	< 10	9.37	4120	< 1
T25023	201 238	1.16	1.0	20	160	< 0.5	< 2	0.64	< 0.5	14	19	65	4.82	< 10	< 1	0.12	30	0.75	2060	3
T25024	201 238	0.40	< 0.2	< 5	190	< 0.5	< 2	12.30	< 0.5	< 1	7	18	3.52	< 10	< 1	0.03	< 10	7.58	3890	< 1
T25025	201 238	1.19	< 0.2	30	310	< 0.5	< 2	3.70	< 0.5	11	18	39	6.66	< 10	1	0.07	10	2.40	6390	< 1
T25026	201 238	0.76	< 0.2	10	170	< 0.5	< 2	6.74	< 0.5	7	11	61	7.37	< 10	< 1	0.05	< 10	3.99	6100	< 1
T25027	201 238	0.99	1.0	20	90	< 0.5	< 2	1.03	0.5	12	20	30	3.45	< 10	< 1	0.08	30	0.70	835	< 1
T25028	217 238	0.45	0.2	25	80	< 0.5	< 2	0.50	1.0	9	52	8	2.81	< 10	< 1	0.18	30	0.22	2150	< 1
T25029	201 238	0.62	0.6	10	70	< 0.5	< 2	2.16	1.0	10	12	20	2.74	< 10	< 1	0.06	20	1.32	1850	< 1
T25030	217 238	0.52	< 0.2	20	40	< 0.5	< 2	2.16	4.0	24	34	93	4.12	< 10	< 1	0.17	10	1.25	2200	< 1
T25031	203 238	1.15	< 0.2	20	80	< 0.5	< 2	3.04	3.0	30	75	110	5.25	< 10	1	0.22	10	2.27	2700	< 1
T25032	203 238	1.03	< 0.2	5	70	< 0.5	< 2	4.00	4.5	23	64	185	5.80	< 10	< 1	0.19	< 10	2.67	3520	< 1
T25033	217 238	0.88	< 0.2	20	90	< 0.5	< 2	1.73	2.5	23	46	83	3.89	< 10	< 1	0.14	10	1.15	2180	< 1
T25034	217 238	0.94	0.2	20	90	< 0.5	< 2	1.27	3.5	20	43	33	3.83	< 10	< 1	0.10	10	0.79	2260	< 1
T25035	201 238	0.91	1.6	30	90	< 0.5	< 2	0.86	2.0	12	13	37	4.81	< 10	2	0.04	20	0.54	2590	1
T25036	217 238	1.34	0.8	25	170	< 0.5	< 2	1.08	2.0	16	42	33	3.80	< 10	< 1	0.11	10	0.46	3380	< 1
T25037	201 238	1.22	1.4	10	100	< 0.5	< 2	0.45	0.5	9	24	25	3.54	< 10	< 1	0.05	20	0.43	1055	< 1
T25038	217 238	0.68	< 0.2	20	130	< 0.5	< 2	0.34	< 0.5	10	27	15	3.57	< 10	1	0.20	30	0.32	2640	< 1
T25039	217 238	1.76	< 0.2	45	240	< 0.5	< 2	0.37	< 0.5	16	64	10	4.05	< 10	2	0.14	30	0.52	3250	< 1
T25040	201 238	2.08	< 0.2	30	130	< 0.5	< 2	0.35	< 0.5	12	40	20	4.16	< 10	< 1	0.08	20	1.01	2220	< 1
T25041	217 238	2.31	< 0.2	25	80	< 0.5	< 2	0.42	< 0.5	30	110	118	6.03	< 10	< 1	0.13	20	1.82	2920	1
T25042	203 238	0.86	< 0.2	55	70	< 0.5	< 2	7.59	0.5	38	67	95	6.48	< 10	< 1	0.17	< 10	4.57	3560	6
T25043	217 238	1.67	< 0.2	20	90	< 0.5	< 2	0.48	< 0.5	22	93	29	4.36	< 10	< 1	0.11	20	1.24	2600	< 1
T25044	203 238	1.64	0.2	35	190	< 0.5	< 2	0.70	< 0.5	17	62	25	6.09	< 10	< 1	0.13	20	0.52	3940	< 1
T25045	201 238	0.83	< 0.2	30	420	< 0.5	< 2	2.83	< 0.5	10	13	44	5.12	< 10	2	0.07	20	1.71	3370	2
T25046	201 238	1.10	0.2	35	290	< 0.5	< 2	1.93	< 0.5	15	21	55	6.42	< 10	1	0.07	20	1.27	4460	3
T25047	201 238	1.21	< 0.2	25	300	< 0.5	< 2	2.18	< 0.5	13	19	53	6.89	< 10	2	0.06	20	1.32	5810	1
T25048	201 238	1.39	0.6	35	180	< 0.5	< 2	0.47	< 0.5	12	19	41	5.14	< 10	< 1	0.08	30	0.45	1910	2
T25049	201 238	1.40	< 0.2	40	210	< 0.5	< 2	0.89	< 0.5	13	23	47	6.11	< 10	< 1	0.06	20	0.72	4500	3
T25050	201 238	1.60	0.4	20	200	< 0.5	< 2	0.63	< 0.5	12	28	32	5.74	< 10	1	0.08	20	0.66	2680	1
T25051	201 238	1.26	< 0.2	40	100	< 0.5	< 2	0.09	< 0.5	10	19	20	4.80	< 10	3	0.07	20	0.36	1660	3
T25052	201 238	1.44	0.2	35	230	< 0.5	< 2	0.45	< 0.5	13	23	37	5.46	< 10	< 1	0.08	20	0.48	3320	3
T25053	201 238	1.35	0.4	5	220	< 0.5	< 2	0.95	< 0.5	14	27	59	5.15	< 10	< 1	0.08	20	0.63	3690	1
T25054	201 238	1.34	< 0.2	25	130	< 0.5	< 2	1.44	< 0.5	10	20	34	4.07	< 10	< 1	0.10	20	0.64	1340	1
T25055	201 238	1.30	1.0	40	110	< 0.5	< 2	0.56	< 0.5	10	25	54	6.03	10	< 1	0.08	30	0.51	2420	1
T25056	201 238	1.21	2.6	40	110	< 0.5	< 2	0.97	0.5	13	19	64	7.10	< 10	< 1	0.12	30	0.64	3030	< 1
T25057	201 238	1.11	< 0.2	25	260	< 0.5	< 2	3.61	0.5	11	15	53	5.98	< 10	< 1	0.08	10	2.35	4980	3
T25058	201 238	0.75	< 0.2	20	100	< 0.5	< 2	5.58	4.5	8	11	43	3.92	< 10	1	0.04	< 10	3.75	2650	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

113 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDP
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24796	201	238	0.01	25	150	186	10	4	33	< 0.01	< 10	< 10	13	10	7070
T25020	201	238	0.01	9	< 10	12	5	1	21	< 0.01	< 10	< 10	8	< 10	78
T25021	201	238	0.01	9	120	14	5	2	14	0.01	10	< 10	10	< 10	84
T25022	201	238	0.01	6	50	4	5	2	16	< 0.01	< 10	< 10	9	< 10	54
T25023	201	238	< 0.01	39	310	38	5	7	6	0.01	10	< 10	38	< 10	128
T25024	201	238	0.01	10	190	10	5	2	11	< 0.01	10	< 10	12	< 10	86
T25025	201	238	0.01	25	910	44	5	5	11	0.02	10	< 10	36	< 10	172
T25026	201	238	0.01	18	1030	22	5	4	16	0.01	10	< 10	20	< 10	292
T25027	201	238	0.01	24	1090	322	5	5	30	0.05	< 10	< 10	38	< 10	968
T25028	217	238	< 0.01	13	570	188	< 5	4	5	< 0.01	< 10	< 10	10	< 10	882
T25029	201	238	0.01	16	710	546	< 5	5	12	0.02	< 10	< 10	22	< 10	748
T25030	217	238	< 0.01	30	610	440	5	8	10	< 0.01	< 10	< 10	30	< 10	1920
T25031	203	238	0.01	37	570	546	10	12	11	0.01	10	< 10	55	< 10	1580
T25032	203	238	0.01	33	630	598	5	13	13	< 0.01	10	< 10	46	< 10	2000
T25033	217	238	< 0.01	31	530	396	10	6	10	< 0.01	< 10	< 10	38	< 10	996
T25034	217	238	< 0.01	31	710	348	5	4	13	< 0.01	< 10	< 10	33	< 10	2130
T25035	201	238	< 0.01	24	850	668	5	6	9	0.01	< 10	< 10	32	< 10	1625
T25036	217	238	0.01	20	1310	660	5	4	16	0.01	< 10	< 10	39	< 10	1325
T25037	201	238	< 0.01	22	670	532	5	5	12	0.03	< 10	< 10	45	< 10	572
T25038	217	238	< 0.01	18	600	140	5	4	11	< 0.01	< 10	< 10	15	< 10	386
T25039	217	238	0.01	18	1030	36	5	2	15	0.04	< 10	< 10	69	< 10	132
T25040	201	238	< 0.01	21	890	34	10	3	12	0.06	< 10	< 10	66	< 10	178
T25041	217	238	0.01	66	740	20	10	12	12	0.05	< 10	< 10	106	< 10	250
T25042	203	238	0.01	63	990	272	15	5	31	0.02	20	10	38	< 10	444
T25043	217	238	< 0.01	46	960	10	5	4	10	0.03	< 10	< 10	56	< 10	166
T25044	203	238	0.01	27	1460	38	5	5	12	0.02	20	< 10	66	< 10	198
T25045	201	238	0.01	26	860	62	5	4	14	0.01	10	< 10	23	< 10	318
T25046	201	238	0.01	36	960	82	10	5	20	0.02	10	< 10	32	< 10	272
T25047	201	238	0.01	27	940	92	10	4	18	0.02	< 10	< 10	32	< 10	294
T25048	201	238	0.01	25	810	52	10	6	13	0.03	10	< 10	35	< 10	170
T25049	201	238	0.01	32	1140	66	5	5	14	0.02	10	< 10	37	< 10	494
T25050	201	238	0.01	26	840	48	5	7	14	0.03	10	< 10	44	< 10	160
T25051	201	238	< 0.01	17	460	34	10	2	6	0.03	< 10	< 10	43	< 10	82
T25052	201	238	< 0.01	26	780	48	5	6	11	0.02	10	< 10	36	< 10	148
T25053	201	238	0.01	22	1020	84	5	4	23	0.02	20	< 10	32	< 10	170
T25054	201	238	0.01	22	1440	34	5	3	32	0.02	10	< 10	29	< 10	152
T25055	201	238	< 0.01	24	860	58	5	7	11	0.02	10	< 10	33	< 10	184
T25056	201	238	0.01	28	1010	690	10	7	13	0.02	20	< 10	30	< 10	1315
T25057	201	238	0.01	27	770	234	10	5	16	0.02	10	< 10	34	< 10	856
T25058	201	238	0.01	20	510	800	5	4	16	0.01	< 10	< 10	22	< 10	2960

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25059	201	238	0.66	6.4	70	60	1.0	< 2	6.14	23.5	12	8	54	4.97	< 10	5	0.04	< 10	4.05	2280	1
T25060	201	238	0.75	< 0.2	15	130	1.0	< 2	6.79	3.0	8	14	55	4.14	< 10	< 1	0.05	< 10	4.52	2960	2
T25061	201	238	0.57	< 0.2	45	90	1.0	< 2	7.80	6.5	11	11	53	4.28	< 10	< 1	0.04	< 10	5.02	3090	1
T25062	201	238	0.79	< 0.2	30	120	1.0	< 2	7.39	4.0	13	16	49	4.71	< 10	< 1	0.06	< 10	4.83	2930	2
T25063	201	238	1.28	1.4	15	150	2.5	< 2	1.60	1.0	19	21	43	4.99	10	< 1	0.11	20	1.15	3210	< 1
T25064	201	238	0.45	< 0.2	45	50	1.5	< 2	7.14	3.0	11	9	39	3.51	< 10	< 1	0.05	< 10	4.24	2450	< 1
T25065	201	238	0.56	< 0.2	30	50	1.5	< 2	7.01	10.0	12	10	41	3.99	< 10	< 1	0.06	< 10	4.26	2700	< 1
T25066	201	238	0.76	1.8	40	80	2.0	< 2	6.68	8.5	27	13	56	4.15	< 10	< 1	0.05	< 10	4.10	2920	< 1
T25067	201	238	1.11	1.0	35	200	2.0	< 2	3.31	6.0	15	17	55	5.42	10	2	0.06	10	2.08	3990	1
T25068	201	238	1.36	< 0.2	25	180	2.5	< 2	2.96	< 0.5	17	21	39	5.59	10	< 1	0.08	20	1.98	3760	1
T25069	201	238	1.05	< 0.2	15	140	1.5	< 2	2.39	< 0.5	13	18	23	4.06	< 10	1	0.06	20	1.54	2070	< 1
T25070	201	238	1.56	0.6	20	200	1.5	< 2	0.83	< 0.5	12	24	33	4.37	10	< 1	0.07	20	0.69	1950	1
T25071	201	238	1.69	0.8	15	150	1.5	< 2	0.74	< 0.5	12	24	32	4.21	10	1	0.09	20	0.65	1600	1
T25072	201	238	1.44	1.0	25	120	2.0	< 2	0.55	< 0.5	15	21	37	5.92	10	< 1	0.07	30	0.58	2560	< 1
T25073	201	238	1.65	1.8	40	170	2.0	< 2	0.55	< 0.5	20	28	117	5.68	10	1	0.13	20	1.03	2370	2
T25074	203	238	3.06	0.6	< 5	150	2.0	< 2	0.38	< 0.5	12	76	22	4.99	10	< 1	0.26	30	3.21	2120	< 1
T25075	201	238	0.63	< 0.2	5	100	1.0	< 2	5.09	< 0.5	10	12	39	3.26	< 10	< 1	0.08	< 10	3.12	2170	1
T25076	201	238	1.36	0.8	30	170	2.0	< 2	0.53	< 0.5	16	25	51	4.99	10	< 1	0.09	20	0.66	2520	1
T25077	201	238	1.36	0.6	10	180	1.5	< 2	0.75	< 0.5	14	21	43	5.16	10	< 1	0.05	20	0.47	2490	3
T25078	201	238	1.27	0.8	20	160	1.0	< 2	0.89	< 0.5	13	23	40	4.45	10	< 1	0.07	20	0.52	2240	1
T25079	201	238	0.71	< 0.2	25	330	< 0.5	< 2	6.35	< 0.5	11	17	65	6.43	< 10	< 1	0.05	< 10	3.98	5820	6
T25080	201	238	0.34	< 0.2	10	170	0.5	< 2	11.40	< 0.5	4	6	31	3.91	< 10	< 1	0.04	< 10	7.18	3900	< 1
T25081	201	238	0.25	< 0.2	5	110	< 0.5	< 2	14.85	< 0.5	< 1	4	51	3.34	< 10	< 1	0.03	< 10	8.96	3860	< 1
T25082	201	238	0.28	< 0.2	5	160	< 0.5	< 2	14.00	< 0.5	< 1	6	27	3.02	< 10	< 1	0.04	< 10	8.45	3680	< 1
T25083	201	238	0.30	< 0.2	15	220	< 0.5	< 2	14.80	< 0.5	< 1	9	27	3.93	< 10	< 1	0.02	< 10	9.04	4570	< 1
T25084	201	238	0.42	< 0.2	< 5	90	< 0.5	< 2	12.85	< 0.5	< 1	6	33	2.92	< 10	< 1	0.07	< 10	7.90	2830	1
T25085	201	238	0.25	< 0.2	< 5	70	0.5	< 2	>15.00	< 0.5	< 1	5	10	3.78	< 10	< 1	0.01	< 10	10.05	4360	< 1
T25086	201	238	0.25	< 0.2	< 5	80	< 0.5	< 2	14.75	< 0.5	< 1	5	13	3.03	< 10	< 1	0.02	< 10	8.98	3600	< 1
T25087	201	238	0.36	< 0.2	10	160	0.5	< 2	14.45	< 0.5	< 1	7	14	4.54	< 10	< 1	0.02	< 10	8.83	5280	< 1
T25088	201	238	0.46	< 0.2	10	140	0.5	< 2	10.10	< 0.5	5	7	36	4.82	< 10	< 1	0.04	< 10	6.21	3890	1
T25089	201	238	0.65	< 0.2	25	150	< 0.5	< 2	6.63	< 0.5	5	8	21	11.00	< 10	< 1	0.02	< 10	3.76	>10000	< 1
T25090	201	238	0.23	< 0.2	< 5	60	< 0.5	< 2	14.90	3.0	< 1	5	25	3.95	< 10	< 1	0.01	< 10	9.02	4190	< 1
T25091	201	238	0.25	< 0.2	< 5	50	< 0.5	< 2	>15.00	1.5	< 1	3	34	3.43	< 10	< 1	0.01	< 10	9.61	3570	< 1
T25092	201	238	0.24	< 0.2	< 5	60	< 0.5	< 2	>15.00	< 0.5	< 1	7	31	2.79	< 10	< 1	0.01	< 10	9.95	3350	< 1
T25093	201	238	0.41	< 0.2	15	100	< 0.5	< 2	13.95	< 0.5	< 1	3	12	4.11	< 10	< 1	0.02	< 10	8.50	4400	< 1
T25094	201	238	0.19	< 0.2	< 5	40	< 0.5	< 2	>15.00	< 0.5	< 1	2	14	5.21	< 10	< 1	0.01	< 10	9.06	5370	< 1
T25095	201	238	0.24	< 0.2	5	40	< 0.5	< 2	14.10	< 0.5	< 1	6	27	5.12	< 10	< 1	0.01	< 10	8.28	5000	< 1
T25096	201	238	0.56	< 0.2	10	100	0.5	< 2	10.10	< 0.5	3	11	31	3.70	< 10	< 1	0.07	< 10	6.32	3470	< 1
T25097	201	238	1.31	< 0.2	10	200	1.0	< 2	3.93	< 0.5	10	24	31	5.70	< 10	< 1	0.07	< 10	2.61	4760	< 1
T25098	201	238	1.60	0.6	45	160	3.0	< 2	0.40	< 0.5	11	22	96	9.07	10	< 1	0.11	30	0.41	5360	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER
BRITISH COLUMBIA CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920979
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920979

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25059	201 238	0.01	23	450	4110	15	4	19	0.01	< 10	< 10	19	10	>10000
T25060	201 238	0.01	24	460	406	10	4	19	0.01	< 10	< 10	23	< 10	3260
T25061	201 238	0.01	23	420	962	15	4	23	0.01	< 10	< 10	19	< 10	5240
T25062	201 238	0.01	29	530	796	15	5	24	0.02	10	< 10	24	< 10	3370
T25063	201 238	0.01	30	820	332	5	7	17	0.02	10	< 10	33	< 10	732
T25064	201 238	0.01	21	400	1075	5	4	35	0.01	20	< 10	16	< 10	2630
T25065	201 238	0.01	22	440	1990	10	5	24	0.01	10	< 10	17	10	6070
T25066	201 238	0.01	26	560	3450	15	4	22	0.01	10	< 10	23	< 10	5800
T25067	201 238	0.01	30	710	818	10	5	14	0.02	10	< 10	32	10	6020
T25068	201 238	0.01	30	690	78	5	7	16	0.02	10	< 10	38	< 10	246
T25069	201 238	0.01	23	700	56	5	5	19	0.02	10	< 10	31	< 10	216
T25070	201 238	0.01	24	850	46	10	5	17	0.04	< 10	< 10	41	< 10	150
T25071	201 238	0.01	22	920	54	5	5	23	0.03	< 10	< 10	40	< 10	166
T25072	201 238	0.01	27	880	70	5	7	18	0.02	10	< 10	37	< 10	152
T25073	201 238	0.01	34	730	122	10	9	19	0.02	10	< 10	37	< 10	186
T25074	203 238	0.01	31	700	72	10	12	12	0.02	30	< 10	49	< 10	138
T25075	201 238	0.01	25	720	32	5	4	23	0.01	10	< 10	19	< 10	116
T25076	201 238	< 0.01	34	700	48	5	6	13	0.02	10	< 10	34	< 10	156
T25077	201 238	0.01	29	1100	54	5	4	13	0.01	10	< 10	33	< 10	200
T25078	201 238	0.01	24	1040	52	5	4	17	0.02	20	10	30	< 10	212
T25079	201 238	0.01	38	800	62	10	4	18	0.01	30	10	23	< 10	336
T25080	201 238	0.01	21	260	22	10	3	26	< 0.01	10	< 10	8	< 10	110
T25081	201 238	0.01	11	80	10	5	2	31	< 0.01	10	< 10	7	< 10	98
T25082	201 238	0.01	8	80	16	5	2	27	< 0.01	10	< 10	7	< 10	80
T25083	201 238	0.01	10	50	20	5	2	19	< 0.01	< 10	< 10	8	< 10	82
T25084	201 238	0.01	13	140	16	< 5	2	19	< 0.01	< 10	< 10	11	< 10	78
T25085	201 238	0.01	7	< 10	12	5	2	23	< 0.01	< 10	< 10	6	< 10	60
T25086	201 238	0.01	7	20	8	5	2	17	< 0.01	< 10	< 10	7	< 10	52
T25087	201 238	0.01	10	130	20	5	2	16	0.01	< 10	< 10	11	< 10	82
T25088	201 238	0.01	23	370	62	5	3	22	0.01	< 10	< 10	15	< 10	126
T25089	201 238	0.01	22	1300	44	5	3	22	< 0.01	20	< 10	17	10	282
T25090	201 238	0.01	18	160	160	10	2	30	< 0.01	10	< 10	8	< 10	606
T25091	201 238	0.01	11	< 10	144	5	2	17	< 0.01	< 10	< 10	8	< 10	266
T25092	201 238	0.01	8	< 10	64	5	2	18	< 0.01	20	10	8	< 10	204
T25093	201 238	0.01	11	120	30	5	2	19	0.01	10	< 10	11	< 10	228
T25094	201 238	0.01	8	< 10	14	5	2	37	< 0.01	< 10	< 10	6	< 10	144
T25095	201 238	0.01	9	60	54	5	3	28	< 0.01	10	< 10	10	< 10	180
T25096	201 238	0.01	19	360	56	5	4	32	0.01	< 10	< 10	17	< 10	160
T25097	201 238	0.01	24	740	88	5	5	14	0.02	10	< 10	35	< 10	190
T25098	201 238	< 0.01	27	670	80	15	8	7	0.02	20	< 10	34	< 10	304

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ?CHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page N 1-A
Tot. P. 6
Date 1-AUG-89
Invoice # I-8920980
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25099	201 238	0.76	< 0.2	< 5	120	< 0.5	2	10.05	0.5	7	17	32	3.30	< 10	< 1	0.08	< 10	6.02	2280	1
25100	201 238	1.16	0.4	< 5	170	< 0.5	8	3.64	1.0	12	21	35	4.21	< 10	< 1	0.10	< 10	2.39	2580	< 1
25101	201 238	0.85	0.2	< 5	150	< 0.5	4	4.92	0.5	13	16	37	4.26	< 10	1	0.08	< 10	3.11	3040	< 1
25102	201 238	0.44	< 0.2	< 5	110	< 0.5	2	9.68	0.5	9	8	42	4.38	< 10	< 1	0.06	< 10	5.33	3060	< 1
25103	201 238	0.93	0.6	< 5	190	0.5	< 2	0.77	0.5	14	14	47	6.57	< 10	2	0.09	30	0.41	3760	2
25104	201 238	1.22	0.8	< 5	190	< 0.5	< 2	0.77	1.0	14	17	32	7.17	< 10	2	0.06	30	0.48	4270	< 1
25105	201 238	0.99	0.4	< 5	130	0.5	4	0.48	0.5	16	15	34	4.96	< 10	< 1	0.08	20	0.51	2450	1
25106	201 238	1.35	0.4	10	100	0.5	4	0.52	0.5	13	22	12	4.59	< 10	2	0.05	20	0.47	1300	< 1
25107	201 238	1.07	0.6	< 5	140	< 0.5	2	1.01	0.5	14	18	34	4.46	< 10	3	0.07	20	0.75	2150	1
25108	201 238	1.51	0.4	< 5	120	< 0.5	2	0.48	0.5	35	29	91	5.84	< 10	2	0.10	20	0.99	1655	< 1
25109	201 238	1.07	< 0.2	< 5	330	< 0.5	< 2	3.91	1.5	11	18	55	11.30	< 10	< 1	0.04	< 10	2.13	8910	< 1
25110	201 238	0.86	1.0	5	160	< 0.5	< 2	1.70	1.5	14	12	33	5.16	< 10	2	0.08	20	0.76	3990	< 1
25111	201 238	0.69	2.4	30	80	< 0.5	2	6.72	8.5	16	12	42	4.16	< 10	1	0.06	< 10	4.10	3030	< 1
25112	201 238	0.65	2.8	25	70	< 0.5	4	4.54	7.5	17	13	46	4.59	< 10	3	0.07	< 10	2.77	2750	< 1
25113	201 238	1.09	3.8	< 5	110	< 0.5	4	2.67	2.5	21	21	85	4.90	< 10	2	0.09	10	1.81	2290	< 1
25114	201 238	1.08	2.0	5	150	< 0.5	2	2.03	2.5	17	18	49	5.53	< 10	1	0.07	10	1.27	3690	< 1
25115	201 238	0.74	1.4	15	160	< 0.5	2	4.85	2.0	13	16	38	4.91	< 10	< 1	0.06	< 10	3.06	3340	< 1
25116	201 238	1.53	1.2	< 5	200	< 0.5	6	2.27	1.5	11	25	26	4.78	< 10	< 1	0.05	10	1.63	2680	< 1
25117	201 238	1.70	0.4	< 5	270	< 0.5	< 2	1.45	0.5	12	28	16	4.50	< 10	1	0.05	20	1.15	2410	< 1
25118	201 238	1.31	0.2	< 5	190	< 0.5	< 2	1.04	2.0	15	27	41	5.17	< 10	< 1	0.06	20	0.63	2650	< 1
25119	201 238	1.04	< 0.2	15	140	< 0.5	2	3.81	0.5	11	20	20	4.93	< 10	< 1	0.06	< 10	2.41	2480	< 1
25120	201 238	1.15	1.2	< 5	120	< 0.5	< 2	2.25	2.0	23	23	48	5.70	< 10	2	0.07	10	1.60	2990	< 1
25121	201 238	1.52	0.2	5	120	< 0.5	< 2	3.67	1.0	29	35	51	7.74	< 10	1	0.07	< 10	2.80	3350	< 1
25122	201 238	1.07	< 0.2	20	130	< 0.5	< 2	2.11	0.5	11	19	24	3.49	< 10	< 1	0.06	10	0.83	1975	< 1
25123	201 238	0.78	0.4	< 5	90	< 0.5	< 2	2.41	0.5	12	14	34	3.90	< 10	1	0.08	10	1.33	1475	< 1
25124	201 238	1.45	0.4	15	210	< 0.5	< 2	0.91	< 0.5	14	27	34	6.52	< 10	1	0.08	20	0.66	3150	< 1
25125	201 238	1.52	0.2	20	180	< 0.5	< 2	0.32	< 0.5	12	26	21	4.88	< 10	< 1	0.07	30	0.44	1775	< 1
25126	201 238	1.70	0.2	< 5	220	< 0.5	< 2	0.79	0.5	13	27	25	6.61	< 10	< 1	0.08	20	0.49	3890	< 1
25127	201 238	0.85	0.8	< 5	170	< 0.5	< 2	1.54	0.5	19	14	52	6.08	< 10	1	0.09	20	0.94	3710	< 1
25128	201 238	1.26	0.4	30	190	< 0.5	< 2	0.57	< 0.5	13	22	29	6.88	< 10	1	0.05	20	0.39	4100	< 1
25129	201 238	1.38	0.2	< 5	230	< 0.5	< 2	0.36	0.5	13	19	42	7.55	< 10	2	0.05	20	0.30	5000	< 1
25130	201 238	1.33	< 0.2	< 5	260	< 0.5	< 2	1.96	0.5	12	23	32	6.71	< 10	< 1	0.05	10	1.31	4790	< 1
25131	201 238	1.17	< 0.2	< 5	180	< 0.5	< 2	2.31	0.5	13	21	48	12.15	< 10	< 1	0.04	10	1.42	8500	2
25132	201 238	0.58	< 0.2	15	130	< 0.5	< 2	11.70	< 0.5	4	11	21	5.92	< 10	1	0.03	< 10	7.16	6070	< 1
25133	201 238	0.34	< 0.2	< 5	70	< 0.5	< 2	14.15	0.5	1	7	15	3.84	< 10	< 1	0.02	< 10	8.58	4200	< 1
25134	201 238	0.90	< 0.2	< 5	180	< 0.5	< 2	8.14	1.0	11	18	28	6.28	< 10	1	0.04	< 10	5.04	6480	< 1
25135	201 238	0.30	< 0.2	5	60	< 0.5	< 2	>15.00	1.5	3	9	24	3.79	< 10	2	0.02	< 10	9.46	4110	< 1
25136	201 238	0.29	< 0.2	15	60	< 0.5	< 2	14.80	< 0.5	1	7	12	3.35	< 10	< 1	0.02	< 10	8.89	3390	< 1
25137	201 238	0.19	< 0.2	< 5	50	< 0.5	< 2	>15.00	0.5	1	5	14	2.80	< 10	< 1	0.01	< 10	10.15	3170	< 1
25138	201 238	0.31	< 0.2	15	60	< 0.5	< 2	>15.00	< 0.5	< 1	7	9	2.90	< 10	4	0.02	< 10	9.72	3180	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25099	201 238	0.01	19	470	32	5	4	25	0.02	< 10	< 10	21	20	144
25100	201 238	0.01	26	620	48	5	5	17	0.03	< 10	< 10	35	10	170
25101	201 238	0.01	24	540	82	5	4	17	0.02	< 10	< 10	26	20	204
25102	201 238	0.01	21	450	34	< 5	3	36	0.01	< 10	< 10	13	40	150
25103	201 238	< 0.01	30	890	38	< 5	6	9	0.01	< 10	< 10	29	10	212
25104	201 238	< 0.01	25	1050	56	< 5	6	11	0.01	< 10	< 10	32	10	228
25105	201 238	< 0.01	27	690	114	< 5	7	11	0.02	< 10	< 10	28	10	192
25106	201 238	< 0.01	18	720	70	< 5	5	11	0.02	< 10	< 10	39	10	278
25107	201 238	< 0.01	24	680	40	< 5	5	12	0.02	< 10	< 10	31	10	172
25108	201 238	< 0.01	55	670	56	< 5	15	11	0.01	< 10	< 10	55	20	140
25109	201 238	0.01	25	1060	40	< 5	6	20	0.02	< 10	< 10	37	60	360
25110	201 238	0.01	21	1070	440	5	4	15	0.01	< 10	< 10	27	30	872
25111	201 238	0.01	24	530	1710	10	4	20	0.01	< 10	< 10	22	50	5090
25112	201 238	0.01	25	570	1620	5	5	18	0.01	< 10	< 10	22	40	4940
25113	201 238	0.01	31	600	1245	5	7	15	0.03	< 10	< 10	37	30	1885
25114	201 238	< 0.01	27	780	588	5	5	11	0.01	< 10	< 10	33	30	1595
25115	201 238	0.01	23	610	630	10	5	15	0.01	< 10	< 10	24	40	1555
25116	201 238	0.01	21	570	630	5	5	13	0.03	< 10	< 10	47	30	988
25117	201 238	0.01	21	510	80	< 5	5	14	0.04	< 10	< 10	53	20	230
25118	201 238	0.01	23	1050	142	< 5	5	16	0.02	< 10	< 10	39	20	1160
25119	201 238	0.01	19	750	92	< 5	7	21	0.02	< 10	< 10	38	10	390
25120	201 238	< 0.01	35	870	668	< 5	9	19	0.01	< 10	< 10	42	10	488
25121	201 238	0.01	44	940	136	< 5	21	23	< 0.01	< 10	< 10	67	10	420
25122	201 238	0.01	17	1200	138	< 5	3	27	0.02	< 10	< 10	34	< 10	270
25123	201 238	0.01	23	1030	76	< 5	4	16	0.01	< 10	< 10	25	10	234
25124	201 238	0.01	25	930	76	5	5	15	0.03	< 10	< 10	45	< 10	312
25125	201 238	< 0.01	22	520	38	< 5	5	10	0.03	< 10	< 10	49	< 10	192
25126	201 238	< 0.01	20	1260	50	< 5	5	17	0.03	< 10	< 10	51	< 10	182
25127	201 238	< 0.01	24	800	74	< 5	7	13	0.01	< 10	< 10	24	< 10	160
25128	201 238	< 0.01	22	870	58	< 5	5	11	0.02	< 10	< 10	41	< 10	198
25129	201 238	< 0.01	24	1060	64	< 5	5	11	0.01	< 10	< 10	37	< 10	222
25130	201 238	< 0.01	28	730	62	5	4	11	0.02	< 10	< 10	43	< 10	278
25131	201 238	< 0.01	24	970	60	< 5	4	11	0.02	< 10	< 10	35	< 10	430
25132	201 238	0.01	16	380	20	< 5	3	15	0.01	< 10	< 10	20	30	176
25133	201 238	0.01	5	140	34	5	1	13	0.01	< 10	< 10	8	30	156
25134	201 238	0.01	18	540	38	5	3	16	0.02	< 10	< 10	26	30	226
25135	201 238	0.01	9	60	94	5	1	20	0.01	< 10	< 10	8	20	358
25136	201 238	0.01	6	80	36	5	1	18	0.01	< 10	< 10	8	10	156
25137	201 238	0.01	7	< 10	22	5	1	20	< 0.01	< 10	< 10	5	20	130
25138	201 238	0.01	10	30	28	10	1	18	0.01	< 10	< 10	9	20	126

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

F RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25139	201 238	0.42	< 0.2	20	80	< 0.5	< 2	13.40	< 0.5	3	8	17	3.07	< 10	< 1	0.02	< 10	8.16	3240	< 1
25140	201 238	0.14	26.4	95	10	< 0.5	< 2	11.30	54.5	14	2	82	6.22	< 10	7	0.01	< 10	6.73	3550	< 1
25141	201 238	0.22	116.0	265	10	< 0.5	8	7.49	71.5	25	4	403	10.50	< 10	18	0.01	< 10	4.70	1825	< 1
25142	201 238	0.34	26.4	75	20	< 0.5	< 2	10.05	11.5	12	9	81	3.76	< 10	2	0.04	< 10	6.28	1365	< 1
25143	201 238	0.23	43.0	60	20	< 0.5	4	8.05	19.0	14	6	74	3.06	< 10	5	0.04	< 10	5.00	1285	< 1
25144	201 238	0.33	7.4	30	30	< 0.5	4	5.72	6.0	21	6	44	3.18	< 10	1	0.08	< 10	3.62	1070	< 1
25145	201 238	0.40	11.6	10	40	< 0.5	2	5.81	4.0	16	7	33	2.79	< 10	1	0.12	< 10	3.58	1145	< 1
25146	201 238	0.87	1.4	15	50	0.5	4	4.62	1.0	17	14	45	3.44	< 10	1	0.19	< 10	3.16	1135	< 1
25147	201 238	0.51	0.8	< 5	50	< 0.5	< 2	6.70	2.5	19	10	56	3.35	< 10	1	0.10	< 10	4.18	1590	< 1
25148	201 238	0.57	2.2	60	60	< 0.5	2	5.69	7.0	33	11	57	3.49	< 10	2	0.05	< 10	3.56	2470	< 1
25149	201 238	0.30	< 0.2	30	60	< 0.5	< 2	7.50	1.5	14	8	28	3.77	< 10	< 1	0.04	< 10	4.51	3150	< 1
25150	201 238	0.30	0.4	15	70	< 0.5	2	7.03	1.5	14	7	26	3.17	< 10	< 1	0.04	< 10	4.23	2700	< 1
25151	201 238	0.20	< 0.2	5	50	< 0.5	< 2	9.32	1.5	9	5	23	3.86	< 10	< 1	0.04	< 10	5.64	3840	< 1
25152	201 238	0.24	0.4	20	50	< 0.5	< 2	7.53	1.5	13	3	27	3.13	< 10	< 1	0.04	< 10	4.49	2720	< 1
25153	201 238	0.96	1.0	15	130	< 0.5	< 2	0.68	1.5	16	15	54	5.30	< 10	< 1	0.09	30	0.58	3270	< 1
25154	201 238	1.69	0.4	25	90	< 0.5	< 2	0.62	< 0.5	25	26	83	6.79	< 10	< 1	0.10	20	1.51	3030	< 1
25155	201 238	0.72	0.6	20	130	< 0.5	< 2	1.21	< 0.5	14	19	35	7.22	< 10	1	0.07	20	0.53	4990	< 1
25156	201 238	0.66	0.4	40	110	< 0.5	< 2	1.37	< 0.5	15	17	26	7.12	< 10	< 1	0.06	20	0.66	4560	< 1
25157	201 238	0.90	0.6	35	110	< 0.5	< 2	0.62	< 0.5	19	17	42	5.31	< 10	2	0.08	30	0.46	2690	< 1
25158	201 238	0.70	0.6	30	90	< 0.5	< 2	1.03	< 0.5	13	14	37	5.69	< 10	< 1	0.08	20	0.65	3000	< 1
25159	201 238	0.86	0.4	25	120	< 0.5	< 2	0.85	< 0.5	18	21	42	5.94	< 10	1	0.09	30	0.64	3340	< 1
25160	201 238	1.01	< 0.2	15	80	< 0.5	< 2	1.11	< 0.5	8	12	20	5.45	< 10	2	0.07	20	0.51	2100	< 1
25161	201 238	1.81	0.2	25	140	< 0.5	< 2	0.77	< 0.5	15	26	31	5.89	< 10	< 1	0.12	30	1.54	2840	< 1
25162	201 238	1.72	0.2	5	160	< 0.5	< 2	1.34	0.5	19	29	44	5.42	< 10	< 1	0.13	20	1.49	2780	< 1
25163	201 238	1.74	0.2	20	100	< 0.5	< 2	0.62	< 0.5	11	29	33	4.54	< 10	< 1	0.14	30	1.50	1480	< 1
25164	201 238	0.63	0.4	40	90	< 0.5	< 2	1.08	< 0.5	14	13	40	5.20	< 10	< 1	0.09	30	0.65	2960	< 1
25201	201 238	1.51	1.2	35	180	2.0	< 2	0.10	0.5	74	14	163	9.21	< 10	2	0.18	40	0.72	6240	< 1
25202	201 238	1.56	1.0	55	250	3.0	< 2	0.13	< 0.5	56	18	130	9.64	< 10	1	0.17	30	0.56	7320	< 1
25203	201 238	1.48	1.6	30	710	3.0	< 2	0.13	< 0.5	46	16	196	13.55	< 10	< 1	0.17	40	0.50	>10000	< 1
25204	201 238	0.81	1.6	65	520	1.0	< 2	0.66	0.5	27	14	156	9.12	< 10	1	0.15	30	0.31	5280	14
25205	201 238	0.17	< 0.2	20	350	< 0.5	< 2	>15.00	1.0	5	2	27	4.18	< 10	< 1	0.03	< 10	8.48	4780	< 1
25206	201 238	0.20	< 0.2	< 5	590	< 0.5	< 2	14.25	2.0	3	6	26	4.46	< 10	< 1	0.02	< 10	8.39	4880	< 1
25207	201 238	1.08	0.4	35	450	< 0.5	< 2	2.91	0.5	17	18	53	6.44	< 10	1	0.08	10	1.93	3670	< 1
25208	201 238	0.53	0.4	20	690	0.5	< 2	1.86	0.5	20	8	49	4.62	< 10	< 1	0.07	20	1.12	2790	< 1
25209	201 238	0.57	0.4	35	2490	< 0.5	< 2	4.56	9.5	20	11	56	8.91	< 10	2	0.05	< 10	2.60	8070	< 1
25210	201 238	1.01	0.4	10	240	< 0.5	< 2	0.32	0.5	16	17	39	5.15	< 10	< 1	0.08	30	0.35	2690	< 1
25211	201 238	1.33	0.2	30	150	0.5	< 2	0.19	< 0.5	13	21	35	3.99	< 10	< 1	0.07	20	0.44	1305	< 1
25212	201 238	1.42	0.2	5	150	0.5	< 2	0.23	< 0.5	13	25	30	3.94	< 10	< 1	0.07	20	0.50	1195	< 1
25213	201 238	1.10	< 0.2	30	310	< 0.5	< 2	6.10	< 0.5	18	22	35	4.70	< 10	< 1	0.08	< 10	4.10	3130	< 1
25214	201 238	0.78	< 0.2	35	120	< 0.5	< 2	10.05	< 0.5	10	17	21	4.31	< 10	< 1	0.06	< 10	6.38	3490	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
5125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25139	201 238	0.01	8	220	26	5	1	15	0.01	< 10	< 10	11	20	144
25140	201 238	0.01	29	190	>10000	35	2	28	< 0.01	< 10	< 10	7	120	>10000
25141	201 238	< 0.01	45	320	>10000	170	2	13	< 0.01	< 10	< 10	9	150	>10000
25142	201 238	0.01	20	310	>10000	60	3	19	0.01	< 10	< 10	14	40	8000
25143	201 238	0.01	21	380	>10000	70	4	21	< 0.01	< 10	< 10	10	40	>10000
25144	201 238	0.01	25	480	4200	20	5	18	0.01	< 10	< 10	11	20	4060
25145	201 238	0.01	19	600	8410	20	5	25	0.01	< 10	< 10	13	10	2700
25146	201 238	0.01	23	970	554	5	7	21	0.01	< 10	< 10	23	20	944
25147	201 238	0.01	25	740	550	10	6	23	0.01	< 10	< 10	19	20	1720
25148	201 238	0.01	34	670	1895	5	5	18	0.03	< 10	< 10	24	30	7340
25149	201 238	0.01	15	540	142	5	4	24	0.01	< 10	< 10	12	20	1540
25150	201 238	0.01	17	510	134	5	4	25	0.01	< 10	< 10	12	10	1340
25151	201 238	0.01	13	400	86	5	4	32	< 0.01	< 10	< 10	8	20	808
25152	201 238	0.01	14	490	148	5	4	34	0.01	< 10	< 10	10	20	1210
25153	201 238	< 0.01	23	770	188	< 5	6	14	0.03	< 10	< 10	30	< 10	1165
25154	201 238	< 0.01	39	1010	38	< 5	12	11	0.02	< 10	< 10	59	< 10	262
25155	201 238	< 0.01	23	1180	44	< 5	5	18	0.01	< 10	< 10	27	< 10	156
25156	201 238	< 0.01	24	1040	58	< 5	5	18	0.01	< 10	< 10	23	< 10	156
25157	201 238	0.01	30	1030	36	< 5	5	19	0.03	< 10	< 10	35	< 10	124
25158	201 238	< 0.01	25	850	40	< 5	5	15	0.01	< 10	< 10	23	< 10	100
25159	201 238	0.01	26	900	24	< 5	7	15	0.03	< 10	< 10	36	< 10	126
25160	201 238	< 0.01	12	1700	20	< 5	4	15	0.01	< 10	< 10	24	< 10	106
25161	201 238	< 0.01	25	1000	36	< 5	9	13	0.07	< 10	< 10	67	10	248
25162	201 238	< 0.01	25	1110	26	< 5	7	20	0.10	< 10	< 10	86	10	282
25163	201 238	< 0.01	25	1150	22	< 5	6	11	0.04	< 10	< 10	49	< 10	276
25164	201 238	< 0.01	23	850	30	< 5	5	14	0.01	< 10	< 10	22	< 10	206
25201	201 238	0.01	46	950	58	< 5	11	12	0.01	< 10	< 10	24	< 10	516
25202	201 238	< 0.01	37	1460	54	5	15	12	0.01	< 10	< 10	29	< 10	172
25203	201 238	0.01	46	1780	110	< 5	17	10	0.01	< 10	< 10	28	< 10	296
25204	201 238	< 0.01	47	1700	126	< 5	10	46	< 0.01	< 10	< 10	36	< 10	436
25205	201 238	0.01	16	140	66	5	2	92	< 0.01	< 10	< 10	8	20	558
25206	201 238	0.01	14	90	50	5	2	60	< 0.01	< 10	< 10	9	20	666
25207	201 238	0.01	28	940	78	< 5	5	17	0.01	< 10	< 10	28	20	512
25208	201 238	0.01	21	670	68	5	7	17	0.01	< 10	< 10	13	10	412
25209	201 238	0.01	39	830	274	< 5	5	40	< 0.01	< 10	< 10	35	30	2390
25210	201 238	< 0.01	22	660	60	< 5	5	8	0.01	< 10	< 10	26	< 10	256
25211	201 238	< 0.01	23	520	34	< 5	4	7	0.02	< 10	< 10	29	< 10	146
25212	201 238	< 0.01	25	600	26	< 5	4	10	0.03	< 10	< 10	38	< 10	148
25213	201 238	0.01	30	590	26	5	5	20	0.04	< 10	< 10	37	20	150
25214	201 238	0.01	18	420	6	5	5	18	0.02	< 10	< 10	25	20	106

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25215	201 238	0.53	< 0.2	10	50	< 0.5	< 2	11.40	< 0.5	11	10	25	4.03	< 10	< 1	0.08	< 10	7.15	2520	< 1
25216	201 238	0.85	< 0.2	20	90	< 0.5	< 2	8.50	< 0.5	18	21	43	5.93	< 10	< 1	0.11	< 10	5.44	3980	< 1
25217	201 238	0.69	< 0.2	15	70	< 0.5	2	7.80	< 0.5	17	14	35	5.24	< 10	< 1	0.07	< 10	5.03	3910	< 1
25218	201 238	0.54	< 0.2	15	40	< 0.5	< 2	11.60	< 0.5	14	13	20	4.91	< 10	< 1	0.06	< 10	7.35	2850	< 1
25219	201 238	0.19	< 0.2	5	30	< 0.5	< 2	>15.00	< 0.5	< 1	5	6	2.88	< 10	< 1	0.03	< 10	9.35	3100	< 1
25220	201 238	0.47	< 0.2	< 5	60	< 0.5	< 2	14.00	0.5	3	7	5	4.52	< 10	< 1	0.04	< 10	8.54	4680	< 1
25221	201 238	1.33	0.2	15	400	< 0.5	< 2	1.95	0.5	14	18	24	7.87	< 10	< 1	0.08	20	1.53	6840	< 1
25222	201 238	0.99	< 0.2	15	90	< 0.5	< 2	8.93	< 0.5	9	11	13	6.35	< 10	1	0.06	< 10	6.04	5090	< 1
25223	201 238	0.18	< 0.2	115	30	< 0.5	< 2	10.25	< 0.5	20	5	23	6.13	< 10	< 1	0.04	< 10	6.27	2240	< 1
25224	201 238	0.73	0.4	70	90	< 0.5	< 2	3.64	< 0.5	22	12	24	5.97	< 10	< 1	0.09	< 10	2.55	2560	3
25225	201 238	0.77	< 0.2	115	110	< 0.5	< 2	6.33	< 0.5	18	13	21	6.39	< 10	< 1	0.06	< 10	4.28	3690	< 1
25226	201 238	0.20	< 0.2	20	40	< 0.5	< 2	13.95	< 0.5	3	5	19	3.78	< 10	1	0.02	< 10	8.50	3790	< 1
25227	201 238	0.25	< 0.2	20	50	< 0.5	< 2	13.45	< 0.5	5	4	17	4.23	< 10	< 1	0.02	< 10	8.14	4160	< 1
25228	201 238	0.39	< 0.2	25	80	< 0.5	< 2	12.05	< 0.5	3	5	8	4.40	< 10	< 1	0.01	< 10	7.36	4940	< 1
25229	201 238	0.42	< 0.2	35	80	< 0.5	< 2	11.35	< 0.5	10	7	9	5.47	< 10	< 1	0.01	< 10	6.95	5300	< 1
25230	201 238	0.36	< 0.2	60	60	< 0.5	< 2	12.40	< 0.5	9	3	7	5.45	< 10	1	0.02	< 10	7.50	5530	< 1
25231	201 238	0.42	< 0.2	70	50	< 0.5	< 2	13.05	< 0.5	25	11	14	5.54	< 10	< 1	0.04	< 10	8.16	3950	< 1
25232	201 238	0.70	< 0.2	40	110	< 0.5	< 2	4.62	< 0.5	64	15	23	8.46	< 10	< 1	0.11	< 10	2.76	5500	< 1
25233	201 238	0.33	< 0.2	20	50	< 0.5	< 2	12.70	< 0.5	21	8	8	3.83	< 10	< 1	0.07	< 10	7.82	3060	< 1
25234	201 238	0.45	< 0.2	30	90	< 0.5	< 2	9.97	< 0.5	18	9	19	4.91	< 10	< 1	0.11	< 10	6.12	3560	< 1
25235	201 238	1.82	0.2	20	420	< 0.5	< 2	0.30	< 0.5	11	28	27	5.83	< 10	< 1	0.05	20	0.51	2250	< 1
25236	201 238	1.93	0.2	30	380	0.5	< 2	0.20	< 0.5	17	28	39	4.83	< 10	< 1	0.07	20	0.64	1950	< 1
25237	201 238	1.52	0.2	25	220	< 0.5	< 2	0.30	< 0.5	23	19	48	5.25	< 10	1	0.10	20	0.59	2460	< 1
25238	201 238	0.95	0.2	15	330	< 0.5	< 2	4.56	0.5	20	13	58	5.37	< 10	3	0.10	< 10	3.07	3770	< 1
25239	201 238	1.42	0.2	30	380	< 0.5	< 2	1.27	< 0.5	16	19	36	9.40	< 10	1	0.09	20	0.58	7150	< 1
25240	201 238	1.42	0.4	30	360	< 0.5	< 2	1.62	< 0.5	21	17	55	9.78	< 10	< 1	0.09	20	1.14	7340	< 1
25241	201 238	0.44	< 0.2	10	150	< 0.5	< 2	10.40	< 0.5	9	8	19	5.57	< 10	1	0.03	< 10	6.31	5910	< 1
25242	201 238	0.91	< 0.2	20	320	< 0.5	< 2	5.15	< 0.5	18	10	38	7.69	< 10	1	0.06	< 10	3.30	6040	< 1
25243	201 238	0.97	0.8	55	290	< 0.5	< 2	1.30	< 0.5	33	13	119	7.84	< 10	1	0.08	30	0.96	5400	1
25244	201 238	0.66	0.2	55	170	< 0.5	< 2	5.82	< 0.5	16	13	161	6.73	< 10	< 1	0.07	< 10	3.48	5320	< 1
25245	201 238	0.26	< 0.2	< 5	70	< 0.5	< 2	13.10	< 0.5	2	7	54	6.53	< 10	< 1	0.01	< 10	7.72	5620	< 1
25246	201 238	1.89	0.2	< 5	170	0.5	< 2	0.11	< 0.5	36	24	73	9.34	< 10	< 1	0.14	20	0.53	6480	< 1
25247	201 238	1.66	1.2	55	160	1.5	< 2	0.14	< 0.5	63	13	155	10.30	< 10	< 1	0.16	30	0.81	7460	2
25248	201 238	1.41	< 0.2	20	60	< 0.5	< 2	0.14	< 0.5	16	20	50	5.90	< 10	< 1	0.09	10	0.26	1935	< 1
25249	201 238	1.69	< 0.2	15	110	< 0.5	< 2	0.06	< 0.5	22	24	51	6.34	< 10	1	0.07	10	0.40	3020	< 1
25250	201 238	1.35	< 0.2	40	180	< 0.5	< 2	0.04	< 0.5	26	24	35	6.73	< 10	1	0.08	10	0.19	4160	< 1
25251	201 238	2.10	< 0.2	40	120	1.0	< 2	0.13	< 0.5	32	24	80	6.61	< 10	< 1	0.08	20	0.61	3160	< 1
25252	201 238	1.27	0.4	30	160	< 0.5	< 2	0.67	< 0.5	21	20	127	7.95	< 10	< 1	0.06	20	0.46	4020	< 1
25253	201 238	1.17	0.6	10	180	0.5	< 2	0.38	0.5	26	16	82	6.41	< 10	2	0.09	30	0.49	4070	< 1
25254	201 238	1.56	0.4	45	150	0.5	< 2	0.50	< 0.5	28	20	89	7.24	< 10	< 1	0.12	20	0.55	3740	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25215	201	238	0.01	21	360	6	5	5	27	0.01	< 10	< 10	21	30	124
25216	201	238	0.01	28	540	22	< 5	8	22	0.01	< 10	< 10	33	30	144
25217	201	238	0.01	20	600	6	5	7	16	< 0.01	< 10	< 10	26	20	166
25218	201	238	0.01	18	350	12	5	6	21	< 0.01	< 10	< 10	22	40	82
25219	201	238	0.01	7	80	< 2	5	2	26	< 0.01	< 10	< 10	5	20	344
25220	201	238	0.01	16	290	< 2	5	3	31	< 0.01	< 10	< 10	8	30	262
25221	201	238	0.01	20	800	36	< 5	5	10	0.02	< 10	< 10	28	10	448
25222	201	238	0.01	26	590	12	5	5	19	0.01	< 10	< 10	16	40	282
25223	201	238	0.01	39	180	46	15	3	27	< 0.01	< 10	< 10	8	30	138
25224	201	238	< 0.01	40	550	46	5	5	11	0.01	< 10	< 10	15	20	210
25225	201	238	0.01	45	460	58	5	4	15	0.01	< 10	< 10	17	20	240
25226	201	238	0.01	11	200	< 2	5	4	23	< 0.01	< 10	< 10	12	20	96
25227	201	238	0.01	15	290	6	< 5	4	21	< 0.01	< 10	< 10	15	30	118
25228	201	238	0.01	11	220	4	5	6	16	0.01	< 10	< 10	13	20	112
25229	201	238	0.01	18	280	8	< 5	4	16	0.01	< 10	< 10	13	30	122
25230	201	238	0.01	20	270	4	5	4	15	< 0.01	< 10	< 10	11	30	92
25231	201	238	0.01	33	200	20	5	5	17	0.01	< 10	< 10	20	40	92
25232	201	238	0.01	58	1000	12	< 5	12	15	< 0.01	< 10	< 10	36	30	116
25233	201	238	0.01	22	400	< 2	5	6	19	< 0.01	< 10	< 10	14	30	54
25234	201	238	0.01	29	690	14	5	9	20	< 0.01	< 10	< 10	22	30	72
25235	201	238	< 0.01	26	910	30	< 5	4	10	0.02	< 10	< 10	48	< 10	202
25236	201	238	< 0.01	31	710	44	< 5	4	11	0.03	< 10	< 10	46	< 10	232
25237	201	238	< 0.01	28	720	58	< 5	4	9	0.02	< 10	< 10	37	< 10	232
25238	201	238	0.01	32	600	92	< 5	4	20	0.02	< 10	< 10	21	30	368
25239	201	238	< 0.01	28	1780	40	< 5	4	12	0.02	< 10	< 10	34	10	314
25240	201	238	< 0.01	32	990	64	< 5	5	15	0.02	< 10	< 10	31	10	314
25241	201	238	0.01	22	560	16	5	2	27	< 0.01	< 10	< 10	14	40	218
25242	201	238	0.01	31	670	46	< 5	4	17	0.01	< 10	< 10	20	40	222
25243	201	238	< 0.01	42	750	82	< 5	8	20	0.01	< 10	< 10	23	10	248
25244	201	238	0.01	32	730	44	5	5	44	0.01	< 10	< 10	32	20	176
25245	201	238	0.01	13	170	14	5	1	39	< 0.01	< 10	< 10	7	50	128
25246	201	238	< 0.01	26	1140	28	< 5	7	8	0.02	< 10	< 10	40	< 10	160
25247	201	238	< 0.01	45	880	50	< 5	13	14	0.01	< 10	< 10	25	< 10	154
25248	201	238	< 0.01	15	2040	12	< 5	1	7	0.01	< 10	< 10	60	< 10	128
25249	201	238	0.01	24	1530	38	< 5	1	7	0.02	< 10	< 10	41	< 10	166
25250	201	238	< 0.01	20	1800	20	< 5	1	5	0.02	< 10	< 10	45	< 10	98
25251	201	238	< 0.01	44	700	16	< 5	5	9	0.02	< 10	< 10	35	< 10	182
25252	201	238	< 0.01	31	1230	36	< 5	9	19	0.01	< 10	< 10	40	< 10	536
25253	201	238	< 0.01	40	850	46	< 5	7	14	0.02	< 10	< 10	28	< 10	242
25254	201	238	< 0.01	36	1010	62	< 5	7	13	0.01	< 10	< 10	32	< 10	228

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: CHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25255	201	238	1.61	0.2	15	150	0.5	< 2	0.29	< 0.5	20	23	51	5.48	< 10	< 1	0.12	20	0.48	1900	< 1
25256	201	238	1.62	0.4	40	170	0.5	< 2	0.44	< 0.5	21	23	103	6.09	< 10	1	0.11	30	0.52	2520	< 1
25257	201	238	1.63	0.4	60	170	< 0.5	< 2	0.70	< 0.5	16	24	85	7.41	< 10	< 1	0.09	20	0.50	3370	< 1
25258	201	238	1.99	0.2	10	130	< 0.5	< 2	0.12	< 0.5	24	28	77	5.84	< 10	< 1	0.12	20	0.55	2430	< 1
25259	201	238	1.95	< 0.2	20	100	< 0.5	< 2	0.08	< 0.5	14	30	30	5.16	< 10	1	0.08	10	0.42	1420	< 1
25260	201	238	1.83	< 0.2	20	70	< 0.5	< 2	0.09	< 0.5	16	26	53	5.01	< 10	< 1	0.08	20	0.54	1295	< 1
25261	201	238	0.52	< 0.2	25	110	< 0.5	< 2	11.25	< 0.5	9	9	26	4.89	< 10	< 1	0.04	< 10	6.95	4240	< 1
25262	201	238	0.68	< 0.2	30	150	< 0.5	< 2	5.11	< 0.5	25	13	13	9.04	< 10	< 1	0.13	< 10	3.19	5760	< 1
25263	201	238	0.82	0.2	75	330	< 0.5	< 2	0.69	< 0.5	41	17	20	10.00	< 10	1	0.17	20	0.56	3940	< 1
25264	201	238	0.35	< 0.2	75	180	< 0.5	< 2	11.30	< 0.5	65	7	13	5.85	< 10	< 1	0.09	< 10	6.88	3770	< 1
25265	201	238	0.29	< 0.2	70	150	< 0.5	< 2	9.32	< 0.5	37	9	13	5.31	< 10	< 1	0.08	< 10	5.54	3360	< 1
25266	201	238	0.53	< 0.2	40	80	< 0.5	< 2	3.62	< 0.5	40	17	15	7.47	< 10	< 1	0.12	< 10	2.06	3610	< 1
25267	201	238	0.44	< 0.2	40	70	< 0.5	2	4.84	< 0.5	128	16	13	6.71	< 10	< 1	0.09	< 10	2.81	3560	< 1
25268	201	238	0.24	< 0.2	30	40	< 0.5	< 2	9.98	< 0.5	82	9	8	4.65	< 10	< 1	0.05	< 10	5.72	3470	< 1
25269	201	238	0.38	< 0.2	75	80	< 0.5	< 2	12.70	< 0.5	14	9	11	6.14	< 10	< 1	0.01	< 10	7.72	5350	< 1
25270	201	238	0.49	< 0.2	95	100	< 0.5	< 2	10.80	< 0.5	35	9	11	7.31	< 10	< 1	0.02	< 10	6.56	5320	< 1
25271	201	238	0.56	< 0.2	35	130	< 0.5	< 2	10.15	< 0.5	18	7	14	7.06	< 10	< 1	0.02	< 10	6.10	6480	< 1
25272	201	238	0.43	< 0.2	15	100	< 0.5	< 2	9.09	0.5	20	9	22	6.26	< 10	< 1	0.04	< 10	5.47	5540	< 1
25273	201	238	0.44	0.2	40	70	< 0.5	< 2	8.47	3.5	24	10	58	6.18	< 10	< 1	0.04	< 10	5.08	4150	< 1
25274	201	238	0.07	< 0.2	< 5	30	< 0.5	< 2	>15.00	< 0.5	< 1	3	2	1.53	< 10	< 1	0.01	< 10	10.35	1450	< 1
25275	201	238	0.29	0.6	30	80	0.5	< 2	10.75	< 0.5	8	6	22	2.93	< 10	< 1	0.04	< 10	6.75	2210	< 1
25276	201	238	0.28	0.8	45	110	< 0.5	2	8.27	2.0	17	6	53	4.49	< 10	< 1	0.04	< 10	5.04	2230	< 1
25277	201	238	0.43	1.8	15	100	< 0.5	< 2	8.33	0.5	12	10	61	4.91	< 10	< 1	0.04	< 10	5.29	3230	< 1
25278	201	238	0.60	3.2	10	100	< 0.5	< 2	0.39	0.5	28	8	53	6.32	< 10	< 1	0.12	40	0.37	3120	< 1
25279	201	238	0.78	1.8	< 5	80	< 0.5	< 2	0.24	0.5	19	14	66	4.43	< 10	< 1	0.16	40	0.44	1925	< 1
25280	201	238	1.30	1.4	< 5	100	< 0.5	< 2	0.54	0.5	18	18	47	6.47	< 10	< 1	0.15	40	0.70	2370	< 1
25281	201	238	0.18	< 0.2	15	70	< 0.5	< 2	13.15	< 0.5	7	14	7	3.85	< 10	< 1	0.02	< 10	8.12	3430	< 1
25282	201	238	0.16	< 0.2	10	50	< 0.5	< 2	14.10	< 0.5	3	7	17	3.43	< 10	< 1	0.02	< 10	8.63	3550	< 1
25283	201	238	0.25	< 0.2	25	70	< 0.5	< 2	14.15	< 0.5	1	8	15	5.95	< 10	< 1	0.01	< 10	8.32	7970	< 1
25284	201	238	0.18	< 0.2	30	50	< 0.5	< 2	14.85	< 0.5	2	5	7	3.55	< 10	< 1	0.01	< 10	9.12	3890	< 1
25285	201	238	0.13	< 0.2	15	30	< 0.5	< 2	>15.00	< 0.5	< 1	2	4	3.33	< 10	< 1	0.01	< 10	9.26	3760	< 1
25286	201	238	0.27	< 0.2	25	50	< 0.5	< 2	13.35	< 0.5	3	1	8	4.60	< 10	< 1	0.03	< 10	8.11	5440	< 1
25287	201	238	0.16	< 0.2	10	40	< 0.5	< 2	>15.00	0.5	3	6	9	3.94	< 10	< 1	0.01	< 10	9.18	4280	< 1
25288	201	238	0.33	< 0.2	< 5	150	< 0.5	< 2	13.70	< 0.5	8	7	13	3.65	< 10	< 1	0.06	< 10	8.44	3950	< 1
25289	201	238	0.16	< 0.2	10	60	< 0.5	< 2	>15.00	< 0.5	< 1	2	53	4.73	< 10	< 1	0.01	< 10	9.56	6410	< 1
25290	201	238	0.80	0.8	15	80	< 0.5	< 2	0.47	< 0.5	17	10	34	4.19	< 10	< 1	0.09	40	0.55	1910	< 1
25291	201	238	1.02	1.0	20	90	< 0.5	< 2	0.28	< 0.5	20	17	44	5.65	< 10	< 1	0.14	40	0.72	1905	< 1
25292	201	238	1.02	0.6	15	130	< 0.5	< 2	0.53	< 0.5	16	15	24	5.69	< 10	< 1	0.11	40	0.54	3360	< 1
25293	201	238	0.63	0.6	15	100	< 0.5	< 2	1.51	0.5	20	9	22	6.51	< 10	2	0.10	40	1.05	3340	< 1
25294	201	238	1.17	2.0	20	170	< 0.5	< 2	0.70	< 0.5	22	17	45	7.72	< 10	1	0.17	50	0.75	4110	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA CANADA V7J-2C1
PHONE (604) 984-0221

T RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25255	201 238	< 0.01	24	1120	22	< 5	2	11	0.02	< 10	< 10	40	< 10	168
25256	201 238	< 0.01	32	1210	34	< 5	5	15	0.03	< 10	< 10	43	< 10	210
25257	201 238	< 0.01	31	1660	24	< 5	5	15	0.02	< 10	< 10	41	< 10	270
25258	201 238	0.01	36	1020	16	< 5	3	12	0.03	< 10	< 10	49	< 10	190
25259	201 238	< 0.01	22	930	14	< 5	1	9	0.04	< 10	< 10	61	< 10	124
25260	201 238	< 0.01	28	820	20	< 5	2	8	0.03	< 10	< 10	40	< 10	146
25261	201 238	0.01	20	370	8	5	2	19	0.02	< 10	< 10	14	< 10	136
25262	201 238	0.01	41	940	36	5	12	13	< 0.01	< 10	< 10	26	< 10	152
25263	201 238	< 0.01	64	1430	60	< 5	19	10	< 0.01	< 10	< 10	40	< 10	190
25264	201 238	0.01	39	640	36	5	7	20	< 0.01	< 10	< 10	19	< 10	96
25265	201 238	0.01	33	880	34	5	8	26	< 0.01	< 10	< 10	20	< 10	108
25266	201 238	< 0.01	49	1300	34	< 5	14	15	< 0.01	< 10	< 10	33	< 10	114
25267	201 238	< 0.01	82	1490	18	5	14	28	< 0.01	< 10	< 10	27	< 10	76
25268	201 238	0.01	37	510	16	5	7	17	< 0.01	< 10	< 10	20	< 10	64
25269	201 238	0.01	23	250	20	5	5	16	0.01	< 10	< 10	14	< 10	118
25270	201 238	0.01	28	370	16	5	7	17	0.01	< 10	< 10	16	< 10	112
25271	201 238	0.01	24	530	20	5	5	16	0.01	< 10	< 10	18	< 10	190
25272	201 238	0.01	23	540	16	5	5	24	0.01	< 10	< 10	17	< 10	258
25273	201 238	0.01	34	520	46	5	5	22	0.01	< 10	< 10	19	< 10	1910
25274	201 238	0.02	3	< 10	14	5	1	29	< 0.01	< 10	< 10	3	< 10	54
25275	201 238	0.01	12	320	118	10	4	23	< 0.01	< 10	< 10	10	< 10	166
25276	201 238	0.01	27	430	234	10	4	32	0.01	< 10	< 10	10	< 10	1400
25277	201 238	0.01	16	450	154	15	4	22	0.01	< 10	< 10	17	< 10	390
25278	201 238	< 0.01	28	690	132	< 5	7	12	0.02	< 10	< 10	16	< 10	184
25279	201 238	< 0.01	24	820	182	< 5	5	19	0.03	< 10	< 10	21	< 10	210
25280	201 238	0.01	23	1680	234	< 5	7	19	0.02	< 10	< 10	26	< 10	222
25281	201 238	0.01	20	170	18	5	3	49	< 0.01	< 10	< 10	14	< 10	74
25282	201 238	0.01	12	220	8	5	3	41	< 0.01	< 10	< 10	8	< 10	64
25283	201 238	0.01	15	1230	20	< 5	15	87	< 0.01	< 10	< 10	13	< 10	74
25284	201 238	0.01	9	70	40	5	2	38	< 0.01	< 10	< 10	6	< 10	84
25285	201 238	0.01	9	40	52	5	2	32	< 0.01	< 10	< 10	4	< 10	94
25286	201 238	0.02	11	370	4	5	4	24	< 0.01	< 10	< 10	7	< 10	52
25287	201 238	0.01	10	110	14	5	2	71	< 0.01	< 10	< 10	6	< 10	166
25288	201 238	0.01	9	510	12	5	3	31	< 0.01	< 10	< 10	11	< 10	54
25289	201 238	0.01	10	450	14	5	11	57	< 0.01	< 10	< 10	10	< 10	68
25290	201 238	< 0.01	23	680	84	< 5	5	11	0.01	< 10	< 10	16	< 10	212
25291	201 238	< 0.01	31	650	84	< 5	7	13	0.04	< 10	< 10	27	< 10	360
25292	201 238	< 0.01	16	980	196	5	6	12	0.01	< 10	< 10	20	< 10	238
25293	201 238	< 0.01	21	830	88	< 5	8	8	0.01	< 10	< 10	15	< 10	290
25294	201 238	< 0.01	26	1100	224	5	10	14	0.01	< 10	< 10	20	< 10	298

CERTIFICATION :

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25295	201 238	1.66	0.4	5	160	0.5	< 2	0.24	< 0.5	25	17	37	5.13	< 10	< 1	0.19	30	0.82	2670	< 1
25296	201 238	0.81	1.0	< 5	100	< 0.5	< 2	0.41	0.5	18	16	44	4.19	< 10	< 1	0.10	40	0.44	1475	< 1
25297	201 238	0.98	1.2	20	220	< 0.5	< 2	0.56	0.5	26	14	67	9.22	< 10	< 1	0.15	40	0.43	5860	< 1
25298	201 238	0.74	1.0	20	60	0.5	< 2	0.43	< 0.5	18	14	90	4.84	< 10	< 1	0.08	30	0.26	1205	1
25299	201 238	1.06	0.8	10	80	< 0.5	< 2	0.22	< 0.5	19	17	42	4.80	< 10	< 1	0.16	40	0.77	1720	< 1
25300	201 238	1.61	3.8	20	110	< 0.5	4	0.30	0.5	25	26	82	6.86	< 10	< 1	0.19	40	1.15	1795	< 1
25301	201 238	0.48	11.8	5	50	< 0.5	< 2	4.63	3.0	15	9	48	5.28	< 10	< 1	0.07	< 10	3.02	3630	< 1
25302	201 238	0.67	4.0	15	120	< 0.5	< 2	0.34	1.0	17	9	62	5.39	< 10	< 1	0.11	30	0.53	3280	< 1
25303	201 238	0.65	1.2	20	120	< 0.5	< 2	0.34	< 0.5	20	7	27	5.78	< 10	< 1	0.13	40	0.45	3650	< 1
25304	201 238	1.77	1.0	30	220	1.5	< 2	0.49	< 0.5	27	22	68	6.27	< 10	< 1	0.22	30	0.84	2430	< 1
25305	201 238	0.82	1.6	55	130	< 0.5	< 2	0.45	4.5	28	7	32	8.09	< 10	< 1	0.08	30	0.41	5000	< 1
25306	201 238	0.87	1.2	25	120	< 0.5	< 2	2.45	4.0	28	13	42	5.65	< 10	< 1	0.10	20	1.76	3590	< 1
25307	201 238	1.84	1.6	20	170	0.5	< 2	0.48	0.5	26	32	37	5.79	< 10	< 1	0.17	30	1.16	1505	< 1
25437	201 238	2.01	0.8	30	140	< 0.5	< 2	0.45	2.0	51	42	113	8.79	< 10	< 1	0.09	20	1.23	2940	< 1
25438	201 238	0.87	0.4	20	110	< 0.5	< 2	1.35	< 0.5	79	31	161	8.92	< 10	< 1	0.15	20	0.95	3420	< 1
25439	201 238	0.14	< 0.2	< 5	40	< 0.5	< 2	>15.00	< 0.5	< 1	4	15	2.78	< 10	< 1	0.01	< 10	9.87	3180	< 1
25440	201 238	0.11	< 0.2	20	40	< 0.5	< 2	>15.00	< 0.5	5	3	8	3.30	< 10	< 1	< 0.01	< 10	10.10	3420	3
25441	201 238	0.17	< 0.2	30	150	< 0.5	< 2	14.65	< 0.5	9	5	173	4.29	< 10	< 1	0.01	< 10	8.94	4610	7
25442	201 238	0.17	< 0.2	35	160	< 0.5	< 2	>15.00	< 0.5	3	6	37	3.44	< 10	< 1	0.01	< 10	9.29	3820	2
25443	201 238	0.17	< 0.2	25	100	< 0.5	< 2	>15.00	< 0.5	4	6	129	3.52	< 10	< 1	0.01	< 10	9.66	3710	2
25444	201 238	0.29	< 0.2	15	100	< 0.5	< 2	14.00	< 0.5	5	7	103	4.78	< 10	< 1	0.01	< 10	8.78	4780	< 1
25445	201 238	0.23	< 0.2	< 5	90	< 0.5	< 2	14.55	< 0.5	11	7	26	3.50	< 10	< 1	0.02	< 10	9.06	3890	< 1
25446	201 238	0.32	< 0.2	20	50	< 0.5	2	9.17	< 0.5	12	5	34	3.35	< 10	< 1	0.10	< 10	5.72	2310	< 1
25447	201 238	0.39	< 0.2	5	80	< 0.5	< 2	9.83	< 0.5	24	10	64	4.52	< 10	< 1	0.11	< 10	6.14	2840	1
25448	201 238	0.63	< 0.2	< 5	140	< 0.5	< 2	7.82	< 0.5	23	14	62	6.02	< 10	< 1	0.11	< 10	5.07	4030	< 1
25449	201 238	0.49	< 0.2	5	130	< 0.5	< 2	9.04	0.5	26	12	78	5.55	< 10	< 1	0.11	< 10	5.67	3770	< 1
25450	201 238	0.34	< 0.2	5	80	< 0.5	< 2	10.55	< 0.5	18	9	57	4.33	< 10	< 1	0.07	< 10	6.62	3190	2
25451	201 238	0.32	< 0.2	20	130	< 0.5	< 2	11.35	< 0.5	16	7	70	4.71	< 10	< 1	0.05	< 10	7.15	3810	1
25452	201 238	0.24	< 0.2	25	140	< 0.5	< 2	13.15	0.5	10	6	73	4.59	< 10	< 1	0.02	< 10	8.30	4340	1
25453	201 238	1.96	0.2	15	150	< 0.5	< 2	0.40	< 0.5	9	26	12	4.60	< 10	< 1	0.07	20	0.57	1105	< 1
25454	201 238	1.01	< 0.2	30	160	< 0.5	< 2	4.69	< 0.5	17	17	18	8.69	< 10	< 1	0.03	< 10	2.94	6850	< 1
25455	201 238	1.86	< 0.2	15	170	< 0.5	< 2	0.26	< 0.5	6	27	24	3.33	< 10	< 1	0.04	20	0.44	465	< 1
25456	201 238	1.64	0.4	5	150	< 0.5	< 2	0.66	< 0.5	8	24	18	5.86	< 10	< 1	0.04	20	0.55	2550	< 1
25457	201 238	1.66	1.2	70	180	< 0.5	< 2	0.34	< 0.5	22	21	50	9.32	< 10	< 1	0.07	40	0.79	4360	1
25458	201 238	0.92	4.6	30	70	< 0.5	< 2	1.59	2.5	32	12	99	5.82	< 10	< 1	0.20	30	1.36	2480	< 1
25459	201 238	0.96	1.0	< 5	60	< 0.5	< 2	0.39	0.5	23	9	43	4.06	< 10	< 1	0.23	30	0.76	1640	1
25460	201 238	0.97	1.8	25	70	< 0.5	< 2	0.84	1.5	12	15	33	4.29	< 10	< 1	0.08	30	0.72	945	< 1
25461	201 238	0.89	0.6	5	90	< 0.5	< 2	0.92	1.0	9	13	16	3.25	< 10	< 1	0.05	10	0.34	1885	< 1
25462	201 238	0.42	2.8	< 5	30	< 0.5	4	5.37	8.0	8	9	20	3.66	< 10	< 1	0.04	< 10	3.31	2040	< 1
25463	201 238	0.38	2.2	< 5	30	< 0.5	2	4.59	9.0	8	7	22	3.76	< 10	< 1	0.03	< 10	2.83	2500	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDF
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25295	201	238	< 0.01	21	1670	184	5	7	8	0.01	< 10	< 10	23	< 10	212
25296	201	238	0.01	24	590	152	5	5	15	0.03	< 10	< 10	25	< 10	260
25297	201	238	< 0.01	31	1440	182	< 5	8	20	0.01	< 10	< 10	21	< 10	532
25298	201	238	< 0.01	22	1120	52	< 5	5	19	0.01	< 10	< 10	22	< 10	138
25299	201	238	< 0.01	24	760	142	< 5	6	9	0.02	< 10	< 10	22	< 10	180
25300	201	238	0.01	32	910	312	5	8	14	0.05	< 10	< 10	36	< 10	272
25301	201	238	0.01	12	500	5310	20	5	11	0.01	< 10	< 10	13	10	1590
25302	201	238	< 0.01	17	550	1820	< 5	6	9	0.01	< 10	< 10	13	< 10	486
25303	201	238	< 0.01	20	680	112	< 5	6	13	0.01	< 10	< 10	12	< 10	166
25304	201	238	0.01	26	1710	346	5	7	14	0.04	< 10	< 10	37	< 10	290
25305	201	238	< 0.01	27	910	440	< 5	6	6	0.01	< 10	< 10	17	< 10	2680
25306	201	238	0.01	21	650	322	5	6	12	0.02	< 10	< 10	21	10	2120
25307	201	238	0.01	35	860	238	5	8	13	0.05	< 10	< 10	42	< 10	356
25437	201	238	< 0.01	54	860	336	< 5	22	28	0.02	< 10	< 10	106	< 10	986
25438	201	238	< 0.01	67	1530	46	< 5	26	20	< 0.01	< 10	< 10	92	< 10	138
25439	201	238	0.01	4	< 10	< 2	5	1	21	< 0.01	< 10	< 10	6	< 10	40
25440	201	238	0.01	10	< 10	4	5	1	23	< 0.01	< 10	< 10	10	< 10	46
25441	201	238	0.01	14	60	12	5	4	28	< 0.01	< 10	< 10	13	< 10	110
25442	201	238	0.01	9	40	10	5	2	17	< 0.01	< 10	< 10	7	< 10	78
25443	201	238	0.01	12	30	4	5	2	23	< 0.01	< 10	< 10	7	< 10	64
25444	201	238	0.01	8	160	12	5	2	26	< 0.01	< 10	< 10	10	< 10	140
25445	201	238	0.01	30	390	16	5	2	22	< 0.01	< 10	< 10	6	< 10	92
25446	201	238	0.01	16	500	30	5	4	37	< 0.01	< 10	< 10	8	< 10	82
25447	201	238	0.01	35	640	34	5	8	44	< 0.01	< 10	< 10	23	< 10	122
25448	201	238	0.01	32	760	34	< 5	11	26	0.01	< 10	< 10	40	< 10	130
25449	201	238	0.01	37	670	50	5	9	38	< 0.01	< 10	< 10	27	< 10	160
25450	201	238	0.01	28	480	38	5	6	35	< 0.01	< 10	< 10	18	< 10	134
25451	201	238	0.01	27	330	44	5	5	31	< 0.01	< 10	< 10	16	< 10	198
25452	201	238	0.01	16	110	104	5	3	23	< 0.01	< 10	< 10	11	< 10	466
25453	201	238	< 0.01	19	810	90	< 5	4	11	0.03	< 10	< 10	47	< 10	344
25454	201	238	0.01	22	800	192	5	5	13	0.02	< 10	< 10	28	< 10	262
25455	201	238	< 0.01	16	700	54	< 5	2	13	0.03	< 10	< 10	44	< 10	130
25456	201	238	< 0.01	20	980	114	< 5	5	10	0.03	< 10	< 10	42	< 10	342
25457	201	238	< 0.01	49	1040	206	15	7	7	0.01	< 10	< 10	40	< 10	142
25458	201	238	< 0.01	29	730	1795	10	6	19	0.01	< 10	< 10	14	< 10	2230
25459	201	238	< 0.01	19	740	136	< 5	4	19	< 0.01	< 10	< 10	14	< 10	254
25460	201	238	< 0.01	22	430	532	5	5	9	0.03	< 10	< 10	28	< 10	1160
25461	201	238	< 0.01	11	1080	296	< 5	4	11	0.02	< 10	< 10	24	< 10	698
25462	201	238	0.01	9	600	1540	5	4	13	0.01	< 10	< 10	14	< 10	3700
25463	201	238	0.01	11	630	1275	5	4	13	< 0.01	< 10	< 10	13	< 10	3630

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
25464	201 238	0.46	4.0	25	40	< 0.5	< 2	10.20	4.5	8	9	24	4.75	< 10	3	0.03	< 10	6.10	3630	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 1-AUG-89
Invoice # : I-8920980
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920980

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
25464	201 238	0.01	16	480	1850	5	3	21	0.01	< 10	< 10	16	< 10	3090

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDP
Comment :

Page : 1-A
Tot. Pages: 5
Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25465	201	238	0.42	< 0.2	35	70	< 0.5	< 2	11.35	< 0.5	7	7	17	5.97	< 10	< 1	0.03	< 10	6.83	6460	< 1
T25466	201	238	0.75	0.2	15	100	< 0.5	< 2	11.35	< 0.5	4	12	8	5.83	< 10	< 1	0.05	< 10	6.95	6190	< 1
T25467	201	238	2.43	0.2	10	210	< 0.5	< 2	0.29	< 0.5	21	38	27	4.60	< 10	< 1	0.10	20	0.62	855	< 1
T25468	201	238	0.95	0.2	< 5	230	< 0.5	< 2	5.09	0.5	14	15	32	9.92	< 10	< 1	0.04	< 10	3.00	>10000	< 1
T25469	201	238	1.71	0.4	15	120	< 0.5	< 2	0.35	< 0.5	10	34	24	5.36	< 10	< 1	0.06	20	0.56	1640	< 1
T25470	201	238	1.19	0.4	45	180	< 0.5	< 2	1.83	< 0.5	16	20	26	9.46	< 10	< 1	0.05	20	0.99	9780	< 1
T25471	201	238	1.54	0.4	25	160	< 0.5	< 2	0.87	< 0.5	14	26	28	6.88	< 10	< 1	0.07	20	0.59	4570	1
T25472	201	238	2.00	0.2	30	230	< 0.5	< 2	0.35	0.5	36	26	19	6.79	< 10	< 1	0.07	30	0.37	4060	1
T25473	201	238	0.29	< 0.2	25	50	< 0.5	< 2	12.15	< 0.5	9	7	14	5.93	< 10	< 1	0.02	< 10	7.29	6300	1
T25474	201	238	0.47	0.6	40	70	< 0.5	< 2	8.61	0.5	21	8	17	7.72	< 10	< 1	0.04	< 10	5.20	7440	2
T25475	201	238	0.28	< 0.2	< 5	70	< 0.5	< 2	13.30	< 0.5	7	2	7	6.24	< 10	< 1	0.01	< 10	8.11	6700	< 1
T25476	201	238	0.27	< 0.2	15	70	< 0.5	< 2	14.20	< 0.5	5	5	5	4.81	< 10	< 1	0.02	< 10	8.58	5060	< 1
T25477	201	238	0.55	2.2	60	50	< 0.5	< 2	8.06	3.0	23	10	34	4.87	< 10	< 1	0.04	< 10	4.89	2510	4
T25478	201	238	1.74	2.4	30	110	0.5	4	0.27	1.5	10	24	14	4.63	< 10	< 1	0.04	20	0.31	1890	< 1
T25479	201	238	0.60	1.2	5	80	< 0.5	2	0.73	3.5	10	10	16	4.28	< 10	< 1	0.03	30	0.31	2600	< 1
T25480	201	238	0.73	0.6	15	70	< 0.5	< 2	0.95	0.5	9	10	16	4.44	< 10	< 1	0.04	20	0.38	1745	< 1
T25481	201	238	0.70	0.6	< 5	100	< 0.5	< 2	1.51	0.5	10	9	21	4.77	< 10	< 1	0.06	10	0.55	2640	< 1
T25482	201	238	0.84	1.0	20	50	< 0.5	< 2	0.53	0.5	14	14	29	5.22	< 10	< 1	0.04	20	0.32	930	< 1
T25483	201	238	0.57	0.6	35	60	< 0.5	6	3.64	1.0	20	10	35	4.54	< 10	< 1	0.04	< 10	2.30	1475	< 1
T25484	201	238	0.55	0.8	10	80	< 0.5	2	2.16	2.0	20	10	35	4.78	< 10	< 1	0.06	10	1.20	2560	< 1
T25485	201	238	0.68	1.2	25	60	0.5	4	1.85	1.0	23	12	40	4.48	< 10	< 1	0.06	20	1.10	1375	1
T25486	201	238	0.92	2.0	20	80	1.0	4	3.57	2.0	26	17	64	4.48	< 10	< 1	0.15	< 10	2.26	1425	< 1
T25487	201	238	0.76	1.2	30	70	0.5	< 2	1.36	1.5	23	13	41	4.88	< 10	< 1	0.06	20	0.84	1970	< 1
T25488	201	238	0.78	1.2	35	90	0.5	< 2	0.99	1.5	31	14	42	5.71	< 10	< 1	0.07	20	0.62	2540	< 1
T25489	201	238	0.98	1.0	5	110	0.5	2	2.51	1.5	20	17	43	5.15	< 10	< 1	0.06	10	1.51	2360	< 1
T25490	201	238	0.64	1.0	10	60	0.5	< 2	1.00	0.5	13	10	37	4.78	< 10	< 1	0.07	20	0.31	1495	< 1
T25491	201	238	0.79	0.6	< 5	80	< 0.5	< 2	0.86	0.5	9	13	62	5.72	< 10	< 1	0.06	20	0.24	2370	< 1
T25492	201	238	0.79	< 0.2	< 5	80	< 0.5	< 2	2.23	0.5	8	10	28	3.65	< 10	< 1	0.05	< 10	0.44	2750	< 1
T25493	201	238	0.55	0.4	20	80	< 0.5	< 2	0.30	< 0.5	12	10	40	6.74	< 10	< 1	0.06	30	0.26	3450	< 1
T25494	201	238	1.22	2.2	20	90	< 0.5	< 2	0.56	0.5	16	20	34	6.50	< 10	< 1	0.09	30	0.45	2080	< 1
T25495	201	238	0.94	1.6	10	90	< 0.5	< 2	1.22	1.5	9	14	19	4.58	< 10	< 1	0.05	20	0.78	1895	< 1
T25496	201	238	0.81	1.2	20	80	< 0.5	< 2	4.14	2.5	9	15	18	4.55	< 10	< 1	0.05	< 10	2.40	2870	< 1
T25497	201	238	1.21	1.2	25	160	< 0.5	< 2	0.72	1.0	16	20	44	7.91	< 10	< 1	0.06	20	0.53	4820	1
T25498	201	238	1.17	0.8	10	120	< 0.5	< 2	0.71	0.5	14	22	45	7.14	< 10	< 1	0.07	20	0.43	3580	< 1
T25499	201	238	1.55	0.4	5	310	< 0.5	< 2	1.04	< 0.5	19	28	32	13.20	< 10	< 1	0.05	20	0.65	>10000	7
T25500	201	238	1.68	0.2	25	170	< 0.5	< 2	1.16	< 0.5	15	21	40	6.81	< 10	< 1	0.07	20	1.22	3840	< 1
T25501	201	238	1.79	0.2	15	200	< 0.5	< 2	0.24	< 0.5	9	25	17	6.11	< 10	< 1	0.07	20	0.32	1980	4
T25502	201	238	1.80	0.2	20	150	< 0.5	< 2	0.09	< 0.5	10	25	24	4.48	< 10	< 1	0.10	20	0.32	1855	1
T25503	201	238	1.60	1.8	< 5	210	< 0.5	< 2	0.78	1.5	11	25	11	4.91	< 10	< 1	0.07	10	0.44	2370	< 1
T25504	201	238	0.53	1.2	< 5	50	0.5	2	4.24	1.5	6	10	4	2.77	< 10	< 1	0.04	< 10	2.34	1285	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-B
Tot. Pages: 5
Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25465	201	238	0.01	16	450	142	5	3	22	< 0.01	< 10	< 10	16	< 10	318
T25466	201	238	0.01	9	480	54	< 5	4	19	0.01	< 10	< 10	25	< 10	140
T25467	201	238	< 0.01	27	770	14	< 5	6	14	0.03	< 10	< 10	75	< 10	102
T25468	201	238	0.01	26	910	58	5	7	26	0.01	< 10	< 10	34	< 10	212
T25469	201	238	< 0.01	25	600	74	< 5	6	12	0.04	< 10	< 10	51	< 10	238
T25470	201	238	0.01	28	1110	154	5	6	16	0.02	< 10	< 10	36	< 10	198
T25471	201	238	< 0.01	30	1300	56	5	5	13	0.03	< 10	< 10	43	< 10	244
T25472	201	238	< 0.01	51	1120	48	< 5	5	12	0.03	< 10	< 10	47	< 10	216
T25473	201	238	0.01	17	290	84	5	5	32	< 0.01	< 10	< 10	20	< 10	204
T25474	201	238	0.01	31	450	200	5	6	32	0.01	< 10	< 10	22	< 10	518
T25475	201	238	0.01	21	400	10	5	4	35	< 0.01	< 10	< 10	16	< 10	72
T25476	201	238	0.01	13	360	16	5	3	45	< 0.01	< 10	< 10	12	< 10	86
T25477	201	238	0.01	34	480	834	5	4	27	0.02	< 10	< 10	20	< 10	2060
T25478	201	238	< 0.01	18	1010	1045	5	3	11	0.03	< 10	< 10	35	< 10	1760
T25479	201	238	< 0.01	16	830	384	< 5	4	7	0.01	< 10	< 10	18	< 10	1680
T25480	201	238	< 0.01	16	930	142	< 5	4	11	0.01	< 10	< 10	21	< 10	628
T25481	201	238	0.01	16	880	122	< 5	4	22	0.01	< 10	< 10	17	< 10	242
T25482	201	238	< 0.01	21	780	174	5	5	9	0.01	< 10	< 10	26	< 10	906
T25483	201	238	0.01	28	530	88	10	4	13	0.01	< 10	< 10	19	< 10	1000
T25484	201	238	0.01	26	740	394	10	4	18	0.01	< 10	< 10	17	< 10	830
T25485	201	238	< 0.01	33	570	218	5	6	7	0.01	< 10	< 10	21	< 10	970
T25486	201	238	0.01	31	620	634	10	8	12	0.02	< 10	< 10	24	< 10	1775
T25487	201	238	0.01	33	840	196	10	6	12	0.02	< 10	< 10	25	< 10	1170
T25488	201	238	< 0.01	41	800	116	5	6	9	0.02	< 10	< 10	25	< 10	1095
T25489	201	238	0.01	32	710	154	10	5	15	0.03	< 10	< 10	32	< 10	620
T25490	201	238	< 0.01	17	920	166	5	5	17	0.01	< 10	< 10	17	< 10	400
T25491	201	238	< 0.01	14	1340	36	5	5	16	0.01	< 10	< 10	18	< 10	152
T25492	201	238	0.01	12	1400	38	< 5	3	28	0.01	< 10	< 10	15	< 10	118
T25493	201	238	< 0.01	20	660	34	< 5	7	10	0.01	< 10	< 10	20	< 10	122
T25494	201	238	0.01	20	1430	488	< 5	7	16	0.03	< 10	< 10	29	< 10	982
T25495	201	238	< 0.01	16	750	366	< 5	5	11	0.02	< 10	< 10	25	< 10	1140
T25496	201	238	0.01	19	920	510	< 5	5	17	0.02	< 10	< 10	21	< 10	1505
T25497	201	238	< 0.01	31	840	352	< 5	8	16	0.03	< 10	< 10	35	< 10	1000
T25498	201	238	< 0.01	22	1040	200	< 5	7	20	0.02	< 10	< 10	30	< 10	600
T25499	201	238	< 0.01	38	1250	58	< 5	21	20	0.02	< 10	< 10	71	< 10	310
T25500	201	238	0.01	31	1160	50	< 5	10	17	0.02	< 10	< 10	41	< 10	136
T25501	201	238	< 0.01	20	820	68	< 5	2	10	0.04	< 10	< 10	64	< 10	228
T25502	201	238	0.01	15	690	80	< 5	3	10	0.04	< 10	< 10	56	< 10	242
T25503	201	238	0.01	18	820	388	< 5	4	16	0.05	< 10	< 10	49	< 10	892
T25504	201	238	< 0.01	6	700	602	< 5	5	21	< 0.01	< 10	< 10	18	< 10	484

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25505	201	238	1.48	1.0	< 5	120	< 0.5	< 2	1.33	3.0	12	25	52	4.89	< 10	< 1	0.07	10	0.85	1435	< 1
T25506			0.75	< 0.2	15	120	< 0.5	< 2	6.61	3.0	7	14	24	3.73	< 10	< 1	0.03	< 10	3.63	2760	< 1
T25507			2.40	0.4	< 5	150	< 0.5	< 2	0.38	0.5	27	37	48	6.47	< 10	< 1	0.07	20	1.72	2100	1
T25508			0.70	0.4	5	100	< 0.5	< 2	1.94	< 0.5	16	13	45	6.23	< 10	< 1	0.03	10	1.05	3510	< 1
T25509			1.24	1.2	20	80	< 0.5	< 2	1.48	1.5	24	21	30	5.27	< 10	< 1	0.05	10	1.42	2200	< 1
T25510			1.21	0.4	25	120	< 0.5	< 2	0.86	< 0.5	22	26	32	8.07	< 10	< 1	0.06	10	0.86	3680	< 1
T25511			0.88	0.6	15	150	< 0.5	4	3.48	0.5	14	15	41	4.80	< 10	< 1	0.10	< 10	2.00	2450	2
T25512			0.49	1.2	45	80	< 0.5	< 2	3.56	0.5	20	10	31	7.80	< 10	< 1	0.04	< 10	1.84	3970	1
T25513			1.13	0.4	15	110	< 0.5	6	1.94	0.5	16	21	19	4.01	< 10	< 1	0.06	10	1.26	1365	< 1
T25514			0.67	< 0.2	5	120	< 0.5	< 2	5.89	0.5	8	10	13	4.38	< 10	< 1	0.06	< 10	2.98	4390	< 1
T25515			0.97	0.2	40	150	< 0.5	2	5.20	< 0.5	25	17	29	6.78	< 10	< 1	0.07	< 10	3.17	3430	3
T25516			1.03	< 0.2	10	210	< 0.5	2	5.45	< 0.5	10	15	26	6.28	< 10	< 1	0.05	< 10	3.20	5460	< 1
T25517			1.23	0.4	10	450	< 0.5	< 2	1.10	0.5	13	22	51	8.02	< 10	< 1	0.06	20	0.63	3960	2
T25518			1.32	0.2	30	190	< 0.5	< 2	4.24	< 0.5	11	22	44	7.88	< 10	< 1	0.05	< 10	2.66	6990	< 1
T25519			0.30	< 0.2	< 5	70	< 0.5	< 2	>15.00	0.5	< 1	6	9	3.18	< 10	< 1	0.02	< 10	9.07	3550	< 1
T25520			1.69	< 0.2	< 5	240	< 0.5	< 2	0.94	1.0	14	27	89	6.66	< 10	< 1	0.04	20	0.73	6880	< 1
T25521			1.24	< 0.2	30	190	< 0.5	< 2	6.52	< 0.5	10	20	30	6.42	< 10	< 1	0.03	< 10	4.01	6010	< 1
T25522			0.37	< 0.2	15	80	< 0.5	< 2	>15.00	< 0.5	1	5	8	3.75	< 10	< 1	< 0.01	< 10	9.19	4340	< 1
T25523			0.75	< 0.2	15	120	< 0.5	< 2	10.35	< 0.5	6	9	28	4.89	< 10	< 1	0.03	< 10	6.03	4790	< 1
T25524			1.38	0.4	10	230	< 0.5	< 2	3.01	1.0	18	23	42	8.48	< 10	< 1	0.04	10	1.87	8120	< 1
T25525			1.37	0.4	30	260	< 0.5	< 2	3.02	0.5	18	18	29	8.15	< 10	< 1	0.06	10	1.35	8360	< 1
T25526			0.58	0.2	10	120	< 0.5	4	6.44	< 0.5	12	9	43	4.14	< 10	< 1	0.07	< 10	3.67	3270	1
T25527			1.73	0.4	5	200	< 0.5	2	1.04	0.5	15	27	36	6.10	< 10	< 1	0.08	20	0.71	3540	< 1
T25528			1.07	0.2	10	250	< 0.5	< 2	4.60	0.5	13	19	31	7.04	< 10	< 1	0.05	< 10	2.80	5250	< 1
T25529			1.67	0.4	15	180	< 0.5	< 2	0.92	< 0.5	11	26	19	3.68	< 10	< 1	0.06	20	0.64	1315	2
T25530			1.02	0.4	10	260	< 0.5	< 2	4.18	0.5	12	14	35	7.70	< 10	< 1	0.04	< 10	2.56	6970	< 1
T25531			1.65	0.2	30	180	< 0.5	< 2	0.55	< 0.5	7	25	15	3.89	< 10	< 1	0.06	20	0.52	645	3
T25532			1.62	0.4	20	320	< 0.5	< 2	3.15	< 0.5	14	26	28	8.99	< 10	< 1	0.06	10	1.97	8620	< 1
T25533			1.79	0.6	25	240	0.5	< 2	0.56	< 0.5	14	22	26	7.45	< 10	< 1	0.06	30	0.42	4350	2
T25534			1.85	0.2	15	230	< 0.5	< 2	0.56	< 0.5	12	27	26	5.68	< 10	< 1	0.07	20	0.57	2550	< 1
T25535			0.69	< 0.2	10	100	< 0.5	< 2	9.51	< 0.5	8	14	24	4.51	< 10	< 1	0.04	< 10	5.87	4480	< 1
T25536			1.47	0.4	5	200	< 0.5	< 2	3.08	< 0.5	11	26	29	6.52	< 10	< 1	0.05	< 10	1.97	4800	< 1
T25537			1.53	0.6	5	340	< 0.5	< 2	0.60	0.5	15	26	64	11.30	< 10	< 1	0.05	30	0.55	7350	< 1
T25538			1.48	0.4	50	240	< 0.5	< 2	0.69	< 0.5	20	24	66	7.25	< 10	< 1	0.08	20	0.57	3340	< 1
T25539			0.61	< 0.2	15	110	< 0.5	2	7.91	< 0.5	10	14	35	3.89	< 10	< 1	0.05	< 10	4.84	2980	< 1
T25540			0.70	< 0.2	5	110	< 0.5	< 2	5.14	0.5	14	14	24	4.64	< 10	< 1	0.05	< 10	3.04	3050	< 1
T25541			1.64	0.6	35	150	0.5	< 2	0.95	< 0.5	17	26	40	6.61	< 10	< 1	0.09	30	0.75	2580	< 1
T25542			1.10	0.4	25	170	< 0.5	< 2	2.44	0.5	11	20	31	3.68	< 10	< 1	0.07	10	0.78	2050	< 1
T25543			0.85	< 0.2	20	90	< 0.5	< 2	6.84	< 0.5	15	14	26	4.09	< 10	< 1	0.14	< 10	4.40	2510	< 1
T25544			1.55	0.8	35	250	< 0.5	< 2	0.86	0.5	40	24	82	9.59	< 10	< 1	0.11	30	0.69	6310	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25505	201	238	0.01	27	910	430	< 5	6	17	0.02	< 10	< 10	38	< 10	2850
T25506	201	238	0.01	11	660	156	< 5	3	30	0.01	< 10	< 10	20	< 10	1510
T25507	201	238	< 0.01	45	630	50	< 5	14	8	0.01	< 10	< 10	60	< 10	156
T25508	201	238	< 0.01	21	750	32	< 5	10	14	< 0.01	< 10	< 10	27	< 10	186
T25509	201	238	< 0.01	30	950	206	5	8	16	< 0.01	< 10	< 10	34	< 10	496
T25510	201	238	< 0.01	32	800	58	< 5	15	11	0.01	< 10	< 10	45	< 10	210
T25511	201	238	0.01	29	910	68	5	5	20	0.02	< 10	< 10	24	< 10	296
T25512	201	238	< 0.01	29	840	48	5	8	17	< 0.01	< 10	< 10	19	< 10	404
T25513	201	238	0.01	23	570	44	< 5	5	17	0.03	< 10	< 10	33	< 10	324
T25514	201	238	0.01	13	820	22	5	2	17	0.02	< 10	< 10	15	< 10	254
T25515	201	238	0.01	32	600	40	5	5	23	0.02	< 10	< 10	25	< 10	154
T25516	201	238	0.01	16	710	20	5	4	17	0.02	< 10	< 10	25	< 10	190
T25517	201	238	< 0.01	27	860	48	< 5	6	16	0.02	< 10	< 10	30	< 10	310
T25518	201	238	0.01	25	720	36	5	4	11	0.03	< 10	< 10	31	< 10	220
T25519	201	238	0.01	6	140	< 2	5	1	12	< 0.01	< 10	< 10	5	< 10	74
T25520	201	238	< 0.01	24	860	24	< 5	4	10	0.04	< 10	< 10	40	< 10	522
T25521	201	238	0.01	20	670	22	< 5	3	14	0.03	< 10	< 10	30	< 10	190
T25522	201	238	0.01	7	80	12	5	1	11	0.01	< 10	< 10	7	< 10	74
T25523	201	238	0.01	13	630	22	< 5	2	14	0.01	< 10	< 10	18	< 10	138
T25524	201	238	0.01	26	930	74	< 5	4	12	0.03	< 10	< 10	34	< 10	370
T25525	201	238	0.01	24	1330	66	5	3	15	0.02	< 10	< 10	33	< 10	340
T25526	201	238	0.01	24	950	36	5	3	18	0.01	< 10	< 10	18	< 10	178
T25527	201	238	0.01	30	1290	44	< 5	5	15	0.04	< 10	< 10	48	< 10	220
T25528	201	238	0.01	27	1080	34	5	4	14	0.02	< 10	< 10	32	< 10	206
T25529	201	238	0.01	23	1190	32	< 5	3	14	0.04	< 10	< 10	48	< 10	100
T25530	201	238	0.01	27	960	38	< 5	3	12	0.01	< 10	< 10	30	< 10	312
T25531	201	238	< 0.01	19	1080	30	< 5	3	10	0.02	< 10	< 10	50	< 10	104
T25532	201	238	0.01	28	1080	28	< 5	4	14	0.03	< 10	< 10	44	< 10	260
T25533	201	238	< 0.01	30	1050	60	< 5	6	11	0.02	< 10	< 10	49	< 10	158
T25534	201	238	< 0.01	20	990	36	< 5	6	11	0.03	< 10	< 10	51	< 10	128
T25535	201	238	0.01	14	450	16	< 5	3	14	0.01	< 10	< 10	19	< 10	96
T25536	201	238	0.01	20	830	22	5	4	11	0.03	< 10	< 10	40	< 10	150
T25537	201	238	< 0.01	37	910	64	< 5	7	10	0.03	< 10	< 10	45	< 10	430
T25538	201	238	< 0.01	31	990	54	5	6	12	0.02	< 10	< 10	40	< 10	346
T25539	201	238	0.01	19	560	22	5	3	23	0.01	< 10	< 10	19	< 10	160
T25540	201	238	0.01	26	620	30	< 5	5	25	0.01	< 10	< 10	26	< 10	156
T25541	201	238	0.01	32	1120	46	< 5	7	16	0.03	< 10	< 10	46	< 10	178
T25542	201	238	0.01	18	1450	22	5	3	20	0.02	< 10	< 10	30	< 10	316
T25543	201	238	0.01	26	570	24	5	5	25	< 0.01	< 10	< 10	20	< 10	154
T25544	201	238	< 0.01	48	1320	58	< 5	11	14	0.02	< 10	< 10	46	< 10	346

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25545	201	238	1.55	0.2	25	120	< 0.5	< 2	0.39	< 0.5	18	38	12	4.53	< 10	< 1	0.17	30	0.93	3380	< 1
T25546	201	238	1.02	0.6	25	230	< 0.5	< 2	2.56	0.5	22	18	43	8.32	< 10	< 1	0.07	10	1.55	7020	< 1
T25547	201	238	1.81	0.2	45	70	< 0.5	< 2	2.36	< 0.5	18	30	40	4.18	< 10	< 1	0.29	20	2.42	1350	< 1
T25548	201	238	0.62	0.6	5	140	0.5	< 2	0.85	1.0	7	14	11	6.08	< 10	< 1	0.04	20	0.31	3110	< 1
T25549	201	238	1.43	0.2	10	130	< 0.5	< 2	1.17	0.5	9	27	12	4.69	< 10	< 1	0.05	10	0.56	2240	< 1
T25550	201	238	1.05	< 0.2	< 5	110	< 0.5	< 2	6.77	0.5	18	49	44	4.58	< 10	< 1	0.26	< 10	4.38	2670	< 1
T25551	201	238	1.03	< 0.2	15	120	< 0.5	< 2	7.04	0.5	19	49	43	4.52	< 10	< 1	0.25	< 10	4.60	2850	1
T25552	201	238	0.41	10.8	130	30	< 0.5	< 2	6.05	8.5	19	7	56	5.34	< 10	< 1	0.05	< 10	3.73	1745	2
T25553	201	238	0.75	1.6	80	40	< 0.5	2	3.74	3.0	58	22	185	6.20	< 10	< 1	0.05	< 10	2.33	1770	< 1
T25554	201	238	0.66	1.0	40	50	< 0.5	2	2.44	2.0	15	12	40	5.06	< 10	< 1	0.06	< 10	1.44	1060	1
T25555	201	238	1.63	0.2	10	100	< 0.5	< 2	0.47	< 0.5	29	32	97	8.03	< 10	< 1	0.05	10	0.61	1700	< 1
T25556	201	238	0.33	0.4	35	30	< 0.5	2	9.44	< 0.5	12	9	34	3.35	< 10	< 1	0.05	< 10	5.78	1230	< 1
T25557	201	238	1.23	0.4	30	150	< 0.5	< 2	1.65	< 0.5	28	34	48	5.75	< 10	< 1	0.21	10	0.96	3230	< 1
T25558	201	238	1.18	0.2	20	100	< 0.5	4	1.69	< 0.5	19	29	29	4.26	< 10	< 1	0.21	20	1.23	2270	< 1
T25559	201	238	0.59	< 0.2	15	50	< 0.5	< 2	6.64	0.5	13	10	43	3.90	< 10	< 1	0.04	< 10	4.15	1895	< 1
T25560	201	238	0.52	0.2	15	100	< 0.5	2	4.08	< 0.5	17	10	25	4.24	< 10	< 1	0.05	< 10	2.29	2650	< 1
T25561	201	238	0.64	0.2	15	110	< 0.5	< 2	3.48	0.5	16	10	35	4.72	< 10	< 1	0.06	< 10	2.06	3320	< 1
T25562	201	238	1.39	0.4	10	160	< 0.5	< 2	0.79	0.5	18	24	45	5.81	< 10	< 1	0.08	20	0.63	2460	< 1
T25563	201	238	1.12	0.4	35	180	< 0.5	< 2	2.01	< 0.5	14	18	34	5.86	< 10	< 1	0.07	20	1.11	4040	< 1
T25564	201	238	1.10	0.4	30	190	< 0.5	< 2	3.60	0.5	20	19	44	5.42	< 10	< 1	0.07	< 10	2.44	3260	< 1
T25565	201	238	0.89	0.8	85	370	< 0.5	< 2	3.44	0.5	22	17	65	7.55	< 10	< 1	0.07	< 10	2.25	3470	< 1
T25566	201	238	0.80	0.6	55	180	< 0.5	< 2	4.06	< 0.5	18	14	47	5.22	< 10	< 1	0.06	< 10	2.56	2550	< 1
T25567	201	238	0.82	0.4	25	90	< 0.5	< 2	2.87	< 0.5	16	15	36	4.46	< 10	< 1	0.06	< 10	1.84	2340	< 1
T25568	201	238	1.35	0.4	25	120	< 0.5	2	1.21	0.5	18	25	37	4.82	< 10	< 1	0.07	20	0.84	2160	< 1
T25569	201	238	2.06	0.2	< 5	120	< 0.5	< 2	0.30	< 0.5	9	33	19	6.69	< 10	< 1	0.05	30	0.46	3370	< 1
T25570	201	238	0.72	< 0.2	25	90	< 0.5	< 2	10.85	< 0.5	3	14	23	3.56	< 10	< 1	0.03	< 10	6.98	3260	< 1
T25571	201	238	0.87	< 0.2	25	80	< 0.5	< 2	7.18	< 0.5	11	19	42	3.82	< 10	< 1	0.07	< 10	4.74	2650	< 1
T25572	201	238	0.97	< 0.2	10	90	< 0.5	< 2	5.94	0.5	13	20	52	4.96	< 10	< 1	0.08	< 10	3.82	2800	< 1
T25573	201	238	1.28	0.2	10	150	< 0.5	< 2	5.75	1.0	13	19	127	5.91	< 10	< 1	0.07	< 10	3.89	5120	< 1
T25574	201	238	1.19	< 0.2	25	160	< 0.5	< 2	4.81	0.5	13	18	126	5.82	< 10	< 1	0.07	< 10	3.23	4580	< 1
T25575	217	238	1.46	0.4	5	140	< 0.5	< 2	1.17	0.5	14	46	33	4.48	< 10	< 1	0.21	20	1.15	2490	2
T25576	217	238	2.13	0.2	10	70	< 0.5	< 2	0.13	< 0.5	19	64	27	4.48	< 10	< 1	0.36	30	1.19	1360	2
T25577	201	238	0.34	< 0.2	20	40	< 0.5	< 2	14.15	< 0.5	2	8	29	3.02	< 10	< 1	0.03	< 10	8.92	2890	< 1
T25578	201	238	0.55	< 0.2	45	90	< 0.5	< 2	11.35	< 0.5	6	7	45	4.58	< 10	< 1	0.04	< 10	7.19	4550	< 1
T25579	201	238	0.28	< 0.2	20	50	< 0.5	< 2	>15.00	< 0.5	< 1	5	18	3.17	< 10	< 1	0.02	< 10	9.52	3430	< 1
T25580	201	238	0.98	< 0.2	25	100	< 0.5	< 2	9.43	< 0.5	9	14	64	4.32	< 10	< 1	0.07	< 10	6.20	3590	< 1
T25581	201	238	0.84	< 0.2	5	100	< 0.5	< 2	8.87	0.5	9	14	51	4.19	< 10	< 1	0.07	< 10	5.79	3250	< 1
T25582	201	238	0.65	< 0.2	< 5	60	< 0.5	< 2	8.76	0.5	11	10	33	3.18	< 10	< 1	0.06	< 10	5.74	1805	< 1
T25583	201	238	0.52	< 0.2	5	50	< 0.5	< 2	7.53	0.5	11	13	30	3.30	< 10	< 1	0.06	< 10	4.75	1550	< 1
T25584	201	238	0.74	0.4	10	90	< 0.5	< 2	4.23	1.0	19	11	46	4.60	< 10	< 1	0.05	< 10	2.72	2380	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25545	201	238	< 0.01	26	470	18	< 5	3	5	< 0.01	< 10	< 10	21	< 10	206
T25546	201	238	< 0.01	31	940	42	5	6	14	0.01	< 10	< 10	32	< 10	312
T25547	201	238	< 0.01	35	490	10	< 5	4	13	< 0.01	< 10	< 10	23	< 10	122
T25548	201	238	< 0.01	11	1090	148	< 5	7	9	< 0.01	< 10	< 10	29	< 10	440
T25549	201	238	0.01	15	1110	46	< 5	4	14	0.02	< 10	< 10	46	< 10	384
T25550	201	238	0.01	28	620	28	5	6	22	0.01	< 10	< 10	26	< 10	178
T25551	201	238	0.01	28	540	34	5	6	28	0.01	< 10	< 10	27	< 10	246
T25552	201	238	< 0.01	52	400	6560	20	4	34	< 0.01	< 10	< 10	14	< 10	6860
T25553	201	238	< 0.01	110	460	828	10	10	50	< 0.01	< 10	< 10	35	< 10	2740
T25554	201	238	< 0.01	26	680	126	5	6	24	0.01	< 10	< 10	25	< 10	2250
T25555	201	238	< 0.01	50	610	52	< 5	9	11	0.01	< 10	< 10	60	< 10	174
T25556	201	238	0.01	27	380	646	10	4	105	< 0.01	< 10	< 10	17	< 10	418
T25557	201	238	0.01	35	1000	68	< 5	6	21	0.01	< 10	< 10	34	< 10	344
T25558	201	238	< 0.01	32	820	16	< 5	4	14	< 0.01	< 10	< 10	23	< 10	202
T25559	201	238	0.01	20	690	44	5	6	42	0.01	< 10	< 10	18	< 10	270
T25560	201	238	< 0.01	22	710	38	5	5	24	< 0.01	< 10	< 10	16	< 10	202
T25561	201	238	< 0.01	21	690	28	< 5	4	16	< 0.01	< 10	< 10	19	< 10	214
T25562	201	238	< 0.01	34	980	34	< 5	6	12	0.02	< 10	< 10	37	< 10	230
T25563	201	238	0.01	20	1020	36	5	3	12	0.02	< 10	< 10	32	< 10	230
T25564	201	238	0.01	36	640	44	5	5	15	0.02	< 10	< 10	31	< 10	236
T25565	201	238	0.01	40	610	60	5	6	17	0.02	< 10	< 10	26	< 10	388
T25566	201	238	0.01	29	620	48	5	5	18	0.01	< 10	< 10	21	< 10	516
T25567	201	238	< 0.01	25	720	34	5	5	15	0.01	< 10	< 10	21	< 10	188
T25568	201	238	< 0.01	31	880	44	< 5	5	14	0.03	< 10	< 10	36	< 10	260
T25569	201	238	< 0.01	18	1130	20	< 5	5	7	0.03	< 10	< 10	48	< 10	198
T25570	201	238	0.01	14	410	16	< 5	3	16	0.01	< 10	< 10	19	< 10	104
T25571	201	238	0.01	25	500	24	5	3	19	0.01	< 10	< 10	21	< 10	162
T25572	201	238	0.01	25	840	36	5	4	20	0.01	< 10	< 10	23	< 10	226
T25573	201	238	0.01	24	780	62	< 5	4	14	0.01	< 10	< 10	25	< 10	348
T25574	201	238	0.01	23	800	64	5	3	13	0.01	< 10	< 10	26	< 10	332
T25575	217	238	0.01	34	740	40	< 5	3	10	0.01	< 10	< 10	32	< 10	162
T25576	217	238	0.01	38	910	40	< 5	3	7	0.02	< 10	< 10	42	< 10	160
T25577	201	238	0.01	10	80	28	5	1	31	< 0.01	< 10	< 10	7	< 10	198
T25578	201	238	0.01	15	360	24	5	2	18	0.01	< 10	< 10	13	< 10	174
T25579	201	238	0.01	7	70	6	5	1	18	< 0.01	< 10	< 10	6	< 10	78
T25580	201	238	0.01	15	380	48	5	3	16	0.01	< 10	< 10	19	< 10	262
T25581	201	238	0.01	19	490	18	< 5	3	21	0.01	< 10	< 10	18	< 10	162
T25582	201	238	0.01	21	300	28	5	3	24	0.01	< 10	< 10	16	< 10	132
T25583	201	238	0.01	20	400	32	5	3	25	0.01	< 10	< 10	14	< 10	158
T25584	201	238	0.01	32	600	46	5	4	19	0.01	< 10	< 10	21	< 10	304

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25585	201	238	0.57	< 0.2	25	50	0.5	< 2	8.52	< 0.5	7	9	33	3.09	< 10	1	0.05	< 10	5.66	1720	< 1
T25586	201	238	1.16	0.2	55	120	< 0.5	< 2	0.92	< 0.5	12	14	41	6.40	< 10	1	0.06	20	0.51	2980	1
T25587	201	238	1.30	0.6	30	160	< 0.5	< 2	0.84	< 0.5	15	23	49	5.89	10	< 1	0.08	20	0.71	3360	< 1
T25588	201	238	1.25	0.2	60	150	< 0.5	< 2	1.55	< 0.5	20	20	41	5.63	< 10	2	0.08	20	1.15	2340	1
T25589	201	238	1.34	0.2	60	160	< 0.5	< 2	0.91	< 0.5	19	22	63	6.41	< 10	< 1	0.06	20	0.61	3060	1
T25590	217	238	0.81	< 0.2	< 5	110	< 0.5	< 2	2.58	< 0.5	11	55	48	3.75	< 10	< 1	0.15	10	1.74	3110	< 1
T25591	203	238	1.15	< 0.2	15	110	< 0.5	< 2	1.24	< 0.5	16	47	35	4.33	< 10	< 1	0.17	20	0.80	2190	1
T25592	201	238	1.29	< 0.2	15	110	< 0.5	< 2	0.64	< 0.5	11	21	23	5.30	< 10	< 1	0.05	20	0.47	2510	< 1
T25593	201	238	1.36	0.2	25	110	< 0.5	< 2	0.49	< 0.5	14	19	23	5.39	< 10	< 1	0.05	20	0.52	2240	< 1
T25594	201	238	0.74	< 0.2	5	90	< 0.5	< 2	6.04	< 0.5	14	13	38	4.66	< 10	< 1	0.08	< 10	3.85	2930	1
T25595	217	238	0.76	< 0.2	5	50	< 0.5	< 2	2.92	< 0.5	19	40	46	4.73	< 10	1	0.17	< 10	1.77	1665	< 1
T25596	201	238	0.73	< 0.2	20	60	< 0.5	< 2	5.84	< 0.5	13	18	40	4.46	< 10	1	0.06	< 10	3.92	1490	< 1
T25597	201	238	1.12	< 0.2	20	130	< 0.5	< 2	3.02	< 0.5	22	23	66	6.27	< 10	< 1	0.08	10	2.09	3100	1
T25598	201	238	0.52	< 0.2	60	50	< 0.5	< 2	6.21	5.0	18	10	49	5.03	< 10	< 1	0.06	< 10	4.02	1800	1
T25599	201	238	0.44	< 0.2	75	20	< 0.5	< 2	8.35	8.0	15	11	53	4.63	< 10	2	0.03	< 10	5.56	1150	< 1
T25600	201	238	0.27	16.8	215	10	< 0.5	< 2	7.87	22.5	25	6	94	7.05	< 10	4	0.02	< 10	5.15	1365	< 1
T25601	201	238	1.60	< 0.2	15	170	< 0.5	< 2	0.58	< 0.5	12	23	29	5.65	< 10	1	0.09	20	0.85	3090	1
T25602	201	238	1.53	< 0.2	20	120	< 0.5	< 2	0.36	< 0.5	11	25	36	4.65	< 10	1	0.11	20	0.70	1550	1
T25603	201	238	1.81	< 0.2	30	170	< 0.5	< 2	0.34	< 0.5	12	43	27	6.25	< 10	1	0.06	10	0.56	2640	2
T25604	201	238	1.15	< 0.2	20	120	< 0.5	< 2	0.36	< 0.5	15	25	50	4.46	< 10	1	0.07	20	0.65	2350	2
T25605	201	238	1.52	< 0.2	45	180	< 0.5	< 2	0.66	< 0.5	19	22	55	7.35	< 10	1	0.07	20	1.08	6460	1
T25606	201	238	0.85	< 0.2	30	120	< 0.5	< 2	4.59	< 0.5	18	16	49	5.98	< 10	1	0.05	< 10	3.01	4470	1
T25607	201	238	0.87	< 0.2	10	140	< 0.5	< 2	0.52	< 0.5	14	15	29	5.32	< 10	1	0.06	30	0.47	4410	< 1
T25608	201	238	1.54	< 0.2	10	120	< 0.5	< 2	0.86	< 0.5	17	23	52	4.61	< 10	1	0.07	30	1.68	3200	< 1
T25609	201	238	1.12	< 0.2	30	140	< 0.5	< 2	1.03	< 0.5	12	13	42	5.58	< 10	3	0.07	20	0.64	3190	1
T25610	201	238	1.00	< 0.2	10	100	< 0.5	< 2	3.56	2.0	11	22	38	3.89	< 10	< 1	0.06	10	2.53	2140	< 1
T25611	201	238	0.67	< 0.2	20	50	< 0.5	< 2	4.87	< 0.5	11	15	43	3.59	< 10	1	0.05	< 10	3.30	1800	< 1
T25612	201	238	0.77	0.6	20	60	< 0.5	< 2	3.88	2.0	12	14	61	3.96	< 10	< 1	0.08	< 10	2.69	2170	< 1
T25613	201	238	0.35	< 0.2	5	40	< 0.5	< 2	5.92	< 0.5	7	8	26	2.13	< 10	< 1	0.06	< 10	3.55	1315	< 1
T25614	201	238	0.78	2.6	5	50	< 0.5	< 2	6.19	3.0	5	15	42	2.89	< 10	1	0.11	< 10	4.23	1200	< 1
T25615	201	238	0.82	11.0	25	60	< 0.5	< 2	6.33	7.5	10	17	48	2.48	< 10	1	0.10	< 10	4.36	1165	< 1
T25616	201	238	0.85	2.4	20	60	< 0.5	< 2	5.81	4.5	9	19	51	2.65	< 10	2	0.12	< 10	4.00	1415	< 1
T25617	201	238	0.70	< 0.2	15	50	< 0.5	< 2	5.11	3.5	8	9	30	4.26	< 10	1	0.16	< 10	3.32	2590	< 1
T25618	201	238	0.97	3.2	15	70	< 0.5	< 2	2.68	5.0	14	12	56	3.99	< 10	< 1	0.23	30	1.79	1515	< 1
T25619	201	238	1.14	1.0	25	100	< 0.5	< 2	4.03	5.0	27	17	64	4.06	< 10	1	0.27	20	2.80	2150	< 1
T25620	201	238	0.33	< 0.2	5	30	< 0.5	< 2	11.95	3.5	< 1	10	34	2.65	< 10	< 1	0.05	< 10	7.78	2000	< 1
T25621	201	238	0.60	6.2	30	40	< 0.5	< 2	5.75	4.0	11	12	43	2.74	< 10	1	0.09	< 10	3.82	1020	< 1
T25622	201	238	0.61	15.6	55	80	< 0.5	< 2	4.89	12.5	15	15	133	3.44	< 10	7	0.09	< 10	3.28	1435	< 1
T25623	201	238	0.71	8.0	30	90	< 0.5	< 2	3.90	2.0	15	10	59	4.09	< 10	< 1	0.18	10	2.65	2370	< 1
T25624	201	238	0.68	28.2	70	40	< 0.5	< 2	5.57	26.0	14	10	126	4.91	< 10	2	0.12	< 10	3.87	2930	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25585	201	238	0.01	17	270	36	5	3	33	0.01	< 10	< 10	15	< 10	150
T25586	201	238	0.01	23	790	60	5	4	13	0.02	< 10	< 10	25	< 10	450
T25587	201	238	0.01	29	720	54	5	5	11	0.02	< 10	< 10	31	< 10	360
T25588	201	238	0.01	36	690	62	5	5	13	0.03	10	< 10	31	< 10	414
T25589	201	238	0.01	36	760	42	10	5	13	0.03	10	< 10	34	< 10	346
T25590	217	238	0.01	19	440	16	5	4	13	0.01	10	< 10	19	< 10	124
T25591	203	238	0.01	25	680	30	< 5	4	11	0.02	10	< 10	23	< 10	360
T25592	201	238	< 0.01	20	870	36	5	5	8	0.02	10	< 10	30	< 10	300
T25593	201	238	< 0.01	23	630	34	< 5	6	7	0.02	10	< 10	31	< 10	1170
T25594	201	238	0.01	19	670	28	< 5	5	18	0.01	30	10	18	< 10	192
T25595	217	238	0.01	32	710	18	5	7	22	< 0.01	10	< 10	28	< 10	582
T25596	201	238	0.01	29	450	60	5	8	44	< 0.01	20	< 10	28	< 10	826
T25597	201	238	< 0.01	35	760	104	5	9	24	0.01	< 10	< 10	35	< 10	634
T25598	201	238	< 0.01	37	420	602	10	5	67	< 0.01	20	10	16	< 10	3510
T25599	201	238	0.01	37	220	4670	15	5	84	< 0.01	20	10	16	< 10	5660
T25600	201	238	0.01	30	210	>10000	45	4	56	< 0.01	20	10	8	< 10	>10000
T25601	201	238	< 0.01	24	1230	222	5	7	13	0.03	< 10	< 10	54	< 10	286
T25602	201	238	< 0.01	23	1300	26	< 5	5	11	0.03	10	< 10	48	< 10	186
T25603	201	238	< 0.01	22	1050	32	5	3	11	0.05	10	< 10	70	< 10	174
T25604	201	238	0.01	28	770	28	< 5	6	13	0.06	10	< 10	45	< 10	136
T25605	201	238	< 0.01	31	1080	90	5	7	12	0.03	10	< 10	41	< 10	250
T25606	201	238	0.01	31	990	104	10	6	24	0.03	10	< 10	31	< 10	158
T25607	201	238	< 0.01	27	880	32	5	6	15	0.03	10	< 10	29	< 10	116
T25608	201	238	0.01	24	900	40	5	8	18	0.04	10	< 10	46	< 10	510
T25609	201	238	< 0.01	23	1080	142	5	7	19	0.02	< 10	< 10	33	< 10	448
T25610	201	238	0.01	23	670	508	5	6	15	0.02	10	< 10	31	< 10	1305
T25611	201	238	0.01	22	550	332	5	5	21	0.01	10	< 10	21	< 10	1245
T25612	201	238	0.01	21	710	848	10	6	18	0.01	20	< 10	23	< 10	2230
T25613	201	238	< 0.01	15	620	272	5	3	37	< 0.01	10	< 10	9	< 10	760
T25614	201	238	0.01	16	450	5090	10	4	16	0.02	20	< 10	24	< 10	3850
T25615	201	238	0.01	18	580	>10000	15	4	21	0.04	20	< 10	29	10	9680
T25616	201	238	0.01	17	510	4470	10	4	20	0.04	20	< 10	29	< 10	4550
T25617	201	238	0.01	14	760	1280	5	6	30	0.01	20	< 10	20	< 10	2170
T25618	201	238	0.01	21	970	2640	10	7	18	0.02	20	< 10	25	< 10	3840
T25619	201	238	0.01	33	1490	2160	15	9	33	0.02	20	< 10	32	< 10	3950
T25620	201	238	0.01	9	70	3140	5	4	27	0.01	20	< 10	11	< 10	2140
T25621	201	238	0.01	20	410	>10000	15	5	20	0.03	20	< 10	21	< 10	6160
T25622	201	238	0.01	23	530	>10000	25	5	18	0.03	20	< 10	21	10	>10000
T25623	201	238	0.01	15	630	4990	20	5	16	0.02	< 10	< 10	18	< 10	1875
T25624	201	238	0.01	23	500	>10000	55	5	20	0.02	< 10	< 10	19	10	>10000

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25625	201	238	1.58	14.6	45	70	< 0.5	< 2	3.08	9.0	20	22	92	5.92	10	3	0.34	30	2.89	3110	< 1
T25951	201	238	0.32	< 0.2	10	80	< 0.5	< 2	12.75	< 0.5	< 1	8	59	3.96	< 10	< 1	0.04	< 10	8.15	3840	< 1
T25952	201	238	0.21	< 0.2	30	230	< 0.5	< 2	13.35	< 0.5	12	7	151	4.20	< 10	< 1	0.06	< 10	8.18	3220	< 1
T25953	201	238	0.18	< 0.2	25	100	< 0.5	< 2	14.35	< 0.5	< 1	8	58	3.28	< 10	< 1	0.03	< 10	9.04	3390	2
T25954	201	238	0.27	< 0.2	10	40	< 0.5	< 2	13.40	< 0.5	< 1	8	19	3.14	< 10	< 1	0.05	< 10	8.59	3040	2
T25955	201	238	1.10	< 0.2	50	160	< 0.5	< 2	5.59	< 0.5	15	17	64	7.29	< 10	< 1	0.13	< 10	3.97	5760	5
T25956	201	238	0.64	< 0.2	25	140	< 0.5	< 2	9.48	< 0.5	11	15	20	6.27	< 10	< 1	0.08	< 10	6.06	6740	11
T25957	201	238	0.57	< 0.2	5	50	< 0.5	< 2	5.92	< 0.5	13	11	42	3.41	< 10	< 1	0.25	< 10	3.88	1960	< 1
T25958	201	238	2.05	1.2	30	140	< 0.5	< 2	0.23	< 0.5	24	28	177	5.60	10	< 1	0.41	30	1.39	3190	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 31-JUL-89
Invoice # : I-8920981
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8920981

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25625	201	238	0.01	29	670	>10000	15	9	19	0.02	10	< 10	23	< 10	5600
T25951	201	238	0.01	13	280	36	5	3	19	< 0.01	10	< 10	12	< 10	118
T25952	201	238	0.01	20	50	102	5	3	41	< 0.01	< 10	< 10	12	< 10	204
T25953	201	238	0.01	15	< 10	22	5	3	31	< 0.01	10	< 10	10	< 10	262
T25954	201	238	0.01	19	10	20	5	3	20	< 0.01	10	< 10	11	< 10	98
T25955	201	238	0.01	41	680	52	5	8	18	0.01	10	< 10	33	< 10	268
T25956	201	238	0.01	19	470	58	5	5	34	0.01	20	10	27	< 10	150
T25957	201	238	0.01	19	580	34	5	4	29	< 0.01	10	< 10	13	< 10	74
T25958	201	238	0.01	24	530	230	10	7	13	0.03	30	< 10	28	< 10	120

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1-A
Tot. pgs: 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T20051	201	238	0.89	< 0.2	390	120	< 0.5	< 2	0.56	3.0	15	7	25	>15.00	< 10	< 1	0.05	20	0.22	215	26
T20052	201	238	1.17	0.6	20	460	0.5	4	0.45	2.0	12	22	37	3.30	< 10	< 1	0.06	20	0.48	330	3
T20053	201	238	0.71	< 0.2	50	380	0.5	< 2	0.75	1.0	10	12	19	>15.00	< 10	< 1	0.03	10	0.38	345	1
T20054	201	238	0.56	< 0.2	115	320	< 0.5	< 2	0.14	4.0	8	4	24	>15.00	< 10	< 1	0.01	10	0.08	580	8
T20055	217	238	0.31	< 0.2	805	160	< 0.5	< 2	0.09	0.5	< 1	6	4	>15.00	< 10	< 1	0.01	10	0.05	50	55
T20056	201	238	1.00	0.8	30	1190	0.5	< 2	0.10	0.5	6	23	73	4.32	< 10	2	0.13	10	0.31	205	17
T20057	201	238	0.81	0.8	65	620	< 0.5	4	0.07	< 0.5	4	20	25	3.47	< 10	1	0.11	20	0.25	185	21
T20058	201	238	0.88	1.0	70	330	< 0.5	2	0.04	< 0.5	3	22	19	3.20	< 10	< 1	0.11	20	0.24	155	42
T20059	201	238	0.70	0.6	35	480	< 0.5	< 2	0.04	< 0.5	3	20	30	2.95	< 10	1	0.11	20	0.20	110	14
T20060	203	238	2.98	< 0.2	180	210	0.5	< 2	0.23	1.5	8	69	240	>15.00	< 10	< 1	0.01	30	4.69	200	62
T20061	201	238	0.93	0.2	20	650	0.5	2	0.66	4.5	9	18	41	2.56	< 10	< 1	0.06	10	0.56	265	7
T20062	201	238	0.88	0.2	< 5	410	0.5	2	0.27	2.0	4	14	39	4.44	< 10	1	0.08	20	0.24	135	4
T20063	203	238	1.00	< 0.2	35	180	1.0	< 2	0.59	21.0	< 1	26	112	>15.00	< 10	1	0.04	20	0.13	85	296
T20064	201	238	1.20	0.8	30	1170	0.5	2	0.67	3.5	11	25	50	4.11	< 10	< 1	0.16	20	0.40	325	25
T20066	201	238	1.64	0.2	90	2600	0.5	2	2.23	9.0	25	21	541	11.40	< 10	< 1	0.03	10	1.34	1105	< 1
T20067	201	238	0.75	< 0.2	210	320	0.5	< 2	0.04	0.5	< 1	24	386	>15.00	< 10	< 1	< 0.01	10	0.05	80	< 1
T20068	201	238	0.79	< 0.2	45	530	0.5	4	6.42	< 0.5	7	23	23	4.25	< 10	< 1	0.06	< 10	3.97	450	1
T20069	201	238	0.96	< 0.2	35	370	< 0.5	6	4.87	0.5	9	29	35	7.18	< 10	< 1	0.07	< 10	2.90	675	1
T20070	201	238	0.54	< 0.2	190	70	< 0.5	< 2	0.24	5.5	28	6	6	>15.00	< 10	< 1	0.03	10	0.12	1545	21
T20077	201	238	1.52	0.2	20	420	< 0.5	4	0.26	1.0	6	30	41	5.33	< 10	< 1	0.11	20	0.57	155	8
T24477	201	238	0.22	< 0.2	50	50	< 0.5	< 2	>15.00	< 0.5	3	11	15	1.66	< 10	< 1	0.05	< 10	9.81	1330	4
T24478	201	238	0.32	< 0.2	55	110	< 0.5	< 2	14.45	0.5	3	12	13	2.70	< 10	< 1	0.04	< 10	9.14	1430	10
T24479	201	238	0.38	0.2	50	130	< 0.5	< 2	14.30	0.5	6	15	17	2.46	< 10	< 1	0.07	< 10	8.99	1320	7
T24480	201	238	0.83	0.6	20	140	1.0	4	4.46	< 0.5	16	18	36	3.27	< 10	< 1	0.09	< 10	2.82	1115	1
T24481	201	238	0.72	0.4	25	160	0.5	< 2	6.43	0.5	13	16	25	3.04	< 10	< 1	0.07	< 10	4.05	1915	2
T24482	201	238	1.24	0.4	10	220	1.0	4	0.93	< 0.5	15	19	50	4.33	< 10	< 1	0.14	30	0.65	1345	< 1
T24483	201	238	1.56	0.2	5	300	1.0	4	1.09	< 0.5	18	22	40	3.79	< 10	< 1	0.21	30	1.09	2020	< 1
T24484	201	238	1.62	0.2	< 5	310	1.0	2	1.64	0.5	19	22	43	3.89	< 10	< 1	0.20	30	1.16	2880	2
T24485	201	238	1.37	0.2	5	210	1.0	6	2.98	0.5	15	22	41	3.78	< 10	< 1	0.16	10	2.07	2200	1
T24486	201	238	0.99	0.4	5	210	1.0	< 2	1.88	0.5	13	18	40	3.90	< 10	< 1	0.18	20	1.18	1360	< 1
T24487	201	238	0.37	< 0.2	40	150	0.5	< 2	11.35	< 0.5	9	13	21	2.40	< 10	< 1	0.06	< 10	6.94	1220	9
T24488	201	238	0.97	1.0	30	260	1.0	4	5.62	0.5	21	21	54	4.37	< 10	< 1	0.08	< 10	3.43	2160	5
T24489	201	238	0.18	< 0.2	55	230	< 0.5	< 2	>15.00	< 0.5	5	9	13	1.68	< 10	< 1	0.04	< 10	10.00	1110	3
T24490	201	238	0.65	< 0.2	15	2920	1.0	< 2	3.59	< 0.5	24	18	96	8.06	< 10	< 1	0.07	10	1.87	9440	< 1
T24491	201	238	1.49	0.2	5	280	1.0	6	1.26	0.5	15	28	39	3.92	< 10	< 1	0.08	20	0.90	2100	2
T24492	201	238	1.44	< 0.2	5	230	2.0	< 2	0.07	0.5	36	25	102	6.38	< 10	< 1	0.08	20	0.48	7760	6
T24493	201	238	0.86	< 0.2	5	410	1.0	< 2	0.17	0.5	38	18	43	7.04	< 10	< 1	0.09	20	0.19	6460	4
T24494	201	238	0.89	< 0.2	< 5	80	< 0.5	< 2	0.10	< 0.5	11	17	13	3.07	< 10	< 1	0.05	10	0.16	1065	< 1
T24495	201	238	1.20	< 0.2	< 5	230	0.5	< 2	0.10	0.5	12	28	24	4.62	< 10	< 1	0.07	10	0.17	1715	1
T24496	201	238	1.18	< 0.2	50	1570	< 0.5	< 2	0.06	< 0.5	19	22	25	7.42	< 10	< 1	0.04	10	0.17	2450	2

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.

125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T20051	201 238	0.01	261	2550	4	< 5	3	96	< 0.01	20	180	38	< 10	3970
T20052	201 238	0.01	46	1030	6	< 5	3	40	0.02	< 10	< 10	37	< 10	340
T20053	201 238	0.01	92	510	22	< 5	3	98	0.01	< 10	< 10	36	< 10	704
T20054	201 238	0.01	62	680	4	< 5	2	19	< 0.01	20	< 10	31	< 10	362
T20055	217 238	0.01	11	3280	20	15	2	10	< 0.01	20	< 10	34	< 10	130
T20056	201 238	0.01	37	1130	20	< 5	4	79	0.01	< 10	< 10	144	< 10	186
T20057	201 238	0.01	18	1250	16	< 5	1	53	0.02	< 10	< 10	189	< 10	96
T20058	201 238	0.01	16	1040	16	< 5	1	45	0.02	< 10	< 10	176	< 10	90
T20059	201 238	0.01	17	740	14	< 5	1	41	0.02	< 10	< 10	176	< 10	82
T20060	203 238	0.01	178	3860	16	< 5	8	507	0.01	10	< 10	487	< 10	1790
T20061	201 238	0.02	45	1020	10	< 5	3	57	0.04	< 10	< 10	49	< 10	308
T20062	201 238	0.01	43	700	8	< 5	1	49	0.01	< 10	< 10	32	< 10	230
T20063	203 238	0.01	81	680	28	20	6	101	< 0.01	20	< 10	313	< 10	570
T20064	201 238	0.01	62	1310	8	< 5	3	73	0.02	< 10	< 10	63	< 10	390
T20066	201 238	0.01	250	1530	22	10	9	958	< 0.01	< 10	< 10	83	< 10	604
T20067	201 238	< 0.01	15	3210	16	< 5	4	217	< 0.01	20	< 10	244	< 10	114
T20068	201 238	0.01	24	730	10	5	3	64	0.07	< 10	< 10	38	< 10	132
T20069	201 238	0.01	34	720	16	< 5	3	59	0.04	< 10	< 10	37	10	188
T20070	201 238	0.01	144	< 10	26	< 5	3	19	< 0.01	30	< 10	30	< 10	1735
T20077	201 238	0.01	32	1320	18	< 5	4	33	0.02	< 10	< 10	48	< 10	160
T24477	201 238	0.02	12	730	144	5	2	81	< 0.01	< 10	< 10	40	< 10	222
T24478	201 238	0.02	15	520	148	10	2	56	< 0.01	< 10	< 10	31	10	364
T24479	201 238	0.02	22	890	404	10	3	64	< 0.01	< 10	< 10	44	10	384
T24480	201 238	0.01	21	1010	178	5	5	32	0.01	< 10	< 10	26	< 10	332
T24481	201 238	0.01	17	910	122	5	3	37	0.01	< 10	< 10	23	10	270
T24482	201 238	0.01	18	1190	48	5	6	20	0.01	< 10	< 10	30	< 10	120
T24483	201 238	0.01	23	1090	26	< 5	6	21	0.02	< 10	< 10	29	< 10	92
T24484	201 238	0.01	23	1560	34	< 5	5	29	0.02	< 10	< 10	28	< 10	102
T24485	201 238	0.01	23	1310	52	5	6	26	0.02	< 10	< 10	33	< 10	130
T24486	201 238	0.01	17	1230	90	5	6	21	0.01	< 10	< 10	25	< 10	204
T24487	201 238	0.02	22	950	78	10	2	54	< 0.01	< 10	< 10	29	10	150
T24488	201 238	0.01	30	1440	140	10	4	31	0.01	< 10	< 10	44	10	284
T24489	201 238	0.02	11	530	70	10	2	74	< 0.01	< 10	< 10	19	10	128
T24490	201 238	0.01	26	720	18	< 5	12	50	0.01	< 10	< 10	49	10	220
T24491	201 238	0.01	27	1320	48	< 5	4	18	0.02	< 10	< 10	40	< 10	172
T24492	201 238	0.01	35	1030	42	< 5	6	9	0.03	< 10	< 10	38	< 10	340
T24493	201 238	0.01	23	1380	52	< 5	2	9	0.01	< 10	< 10	38	< 10	362
T24494	201 238	0.01	10	320	16	< 5	1	8	0.04	< 10	< 10	42	< 10	76
T24495	201 238	0.01	19	1170	40	< 5	1	10	0.02	< 10	< 10	53	< 10	136
T24496	201 238	0.01	38	1020	140	< 5	2	9	0.03	< 10	< 10	47	< 10	226

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ATTN: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 2-A
Tot. : s: 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24497	201	238	0.69	< 0.2	25	460	0.5	< 2	7.29	0.5	18	20	24	6.91	< 10	< 1	0.02	< 10	4.62	5100	< 1
T24498	201	238	0.43	18.2	115	60	0.5	< 2	6.36	13.0	28	10	166	5.30	< 10	1	0.05	< 10	4.04	2020	5
T24607	201	238	0.89	< 0.2	30	100	0.5	< 2	11.60	0.5	4	21	16	1.87	< 10	< 1	0.04	< 10	7.57	1625	13
T24608	201	238	0.31	< 0.2	45	60	< 0.5	< 2	>15.00	< 0.5	< 1	9	10	1.20	< 10	< 1	0.03	< 10	9.81	715	5
T24609	201	238	0.31	< 0.2	40	70	< 0.5	< 2	>15.00	< 0.5	< 1	10	11	0.94	< 10	< 1	0.02	< 10	10.25	1030	3
T24610	201	238	0.92	0.8	15	240	1.0	< 2	4.41	< 0.5	19	27	24	3.76	< 10	< 1	0.08	< 10	2.82	2140	2
T24611	201	238	0.32	< 0.2	60	90	< 0.5	< 2	14.60	< 0.5	6	6	22	2.15	< 10	< 1	0.08	< 10	9.07	895	8
T24612	201	238	0.84	1.6	30	200	1.0	< 2	1.93	1.0	30	16	39	4.54	< 10	< 1	0.08	20	0.89	2340	1
T24613	201	238	0.45	0.6	30	90	0.5	2	5.25	0.5	18	12	29	2.93	< 10	< 1	0.06	< 10	3.06	1635	< 1
T24614	201	238	0.59	0.4	25	140	0.5	< 2	5.27	< 0.5	14	13	30	3.07	< 10	< 1	0.08	< 10	3.27	1550	2
T24615	201	238	0.31	< 0.2	50	130	< 0.5	< 2	12.65	< 0.5	9	8	21	2.16	< 10	< 1	0.06	< 10	7.66	1190	8
T24616	201	238	0.32	< 0.2	40	190	0.5	< 2	13.70	< 0.5	9	13	19	2.09	< 10	< 1	0.04	< 10	8.48	1380	5
T24617	201	238	0.14	< 0.2	35	190	< 0.5	< 2	>15.00	< 0.5	3	9	12	1.53	< 10	< 1	0.02	< 10	10.45	1060	2
T24618	201	238	0.17	< 0.2	45	180	< 0.5	< 2	>15.00	< 0.5	4	8	14	1.59	< 10	< 1	0.02	< 10	10.25	880	3
T24619	201	238	1.07	0.2	15	200	0.5	< 2	3.66	< 0.5	10	19	36	3.23	< 10	< 1	0.09	< 10	2.38	860	1
T24620	201	238	1.03	< 0.2	20	170	0.5	< 2	5.54	< 0.5	11	23	30	3.03	< 10	< 1	0.06	< 10	3.53	1490	2
T24621	201	238	1.06	< 0.2	20	200	< 0.5	< 2	8.01	< 0.5	9	19	25	2.57	< 10	< 1	0.06	< 10	5.07	1460	2
T24622	201	238	1.62	< 0.2	15	190	0.5	2	3.76	< 0.5	11	27	32	3.61	< 10	< 1	0.09	< 10	2.40	1575	5
T24623	201	238	2.01	0.4	< 5	250	1.0	< 2	0.98	1.5	15	31	30	4.98	< 10	< 1	0.10	20	0.57	2460	< 1
T24624	201	238	1.90	1.0	< 5	680	1.5	< 2	0.65	2.0	36	35	75	8.83	< 10	2	0.09	30	0.65	7520	1
T24625	203	238	1.69	< 0.2	5	410	1.0	< 2	0.76	0.5	19	46	27	4.45	< 10	< 1	0.12	20	0.58	2100	4
T24626	201	238	1.37	0.2	5	230	0.5	< 2	0.12	0.5	32	29	29	6.56	< 10	< 1	0.10	20	0.25	4400	1
T24627	201	238	1.52	< 0.2	5	120	0.5	< 2	0.08	< 0.5	20	26	44	4.15	< 10	< 1	0.09	20	0.29	1725	2
T24628	201	238	1.45	0.6	15	270	1.0	2	1.54	< 0.5	19	30	47	6.88	< 10	< 1	0.08	20	0.86	3220	< 1
T24629	201	238	0.62	< 0.2	30	540	< 0.5	< 2	8.08	< 0.5	20	13	23	5.86	< 10	< 1	0.04	< 10	4.63	4440	3
T24630	201	238	1.48	0.8	15	1560	0.5	< 2	0.62	< 0.5	20	34	130	6.34	< 10	< 1	0.06	20	0.53	2370	1
T24631	201	238	0.55	9.8	80	440	< 0.5	< 2	5.35	8.5	29	16	141	5.01	< 10	< 1	0.05	< 10	3.29	2330	2
T24632	201	238	0.40	0.2	25	180	< 0.5	< 2	6.11	< 0.5	13	11	13	4.89	< 10	< 1	0.03	< 10	3.48	4000	< 1
T24671	201	238	0.17	1.4	40	50	< 0.5	< 2	7.89	3.5	16	14	136	3.07	< 10	< 1	0.04	< 10	4.38	2360	< 1
T24672	201	238	0.33	4.0	40	1200	< 0.5	< 2	8.81	3.0	14	16	199	3.48	< 10	< 1	0.05	< 10	5.21	2050	< 1
T24673	201	238	0.96	0.4	25	820	< 0.5	< 2	4.58	0.5	23	26	49	5.35	< 10	< 1	0.08	< 10	2.77	2870	4
T24674	201	238	0.36	< 0.2	35	310	< 0.5	< 2	11.70	< 0.5	13	9	21	5.40	< 10	< 1	0.03	< 10	6.40	3950	2
T24675	201	238	0.47	0.2	20	230	0.5	< 2	8.46	< 0.5	13	10	32	2.91	< 10	< 1	0.05	< 10	4.88	1320	4
T24676	201	238	0.78	< 0.2	25	200	0.5	< 2	8.65	< 0.5	14	17	36	3.14	< 10	< 1	0.08	< 10	5.34	1470	2
T24677	201	238	1.35	0.2	< 5	190	0.5	< 2	0.29	< 0.5	10	27	24	4.20	< 10	< 1	0.09	20	0.34	1000	1
T24678	201	238	1.40	< 0.2	10	130	0.5	< 2	0.13	< 0.5	20	30	44	5.22	< 10	< 1	0.09	20	0.31	1915	4
T24679	201	238	1.68	0.8	20	130	1.0	< 2	0.15	1.0	28	31	81	5.84	< 10	< 1	0.11	20	0.39	3210	1
T24680	201	238	2.01	0.4	5	210	1.0	< 2	0.95	0.5	18	35	45	4.84	< 10	< 1	0.12	30	0.78	2590	< 1
T24681	201	238	1.89	0.4	10	160	1.0	< 2	0.88	< 0.5	16	27	49	4.32	< 10	1	0.10	30	0.85	1955	5
T24682	201	238	1.94	< 0.2	< 5	160	1.0	2	0.34	0.5	21	30	43	4.75	< 10	< 1	0.13	20	0.65	2560	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Page N : 2-B
Tot. I : 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24497	201 238	0.01	41	420	72	5	3	30	0.01	< 10	< 10	22	10	232
T24498	201 238	0.01	39	470	7570	40	5	28	0.01	< 10	< 10	18	30	>10000
T24607	201 238	0.02	17	820	182	5	1	34	0.02	< 10	< 10	37	< 10	392
T24608	201 238	0.02	7	310	48	10	1	62	< 0.01	< 10	< 10	11	< 10	148
T24609	201 238	0.02	8	420	54	5	< 1	48	< 0.01	< 10	< 10	10	< 10	196
T24610	201 238	0.01	28	1090	86	5	6	32	0.01	< 10	< 10	29	< 10	168
T24611	201 238	0.02	16	440	60	10	3	71	< 0.01	< 10	< 10	15	< 10	100
T24612	201 238	0.01	24	1350	512	5	4	27	0.01	< 10	< 10	29	< 10	620
T24613	201 238	0.01	19	820	196	5	4	39	< 0.01	< 10	< 10	16	< 10	334
T24614	201 238	0.01	15	960	122	5	4	33	0.01	< 10	< 10	19	< 10	224
T24615	201 238	0.02	15	800	72	5	3	58	< 0.01	< 10	< 10	21	< 10	138
T24616	201 238	0.02	18	650	74	5	3	64	< 0.01	< 10	< 10	24	< 10	138
T24617	201 238	0.02	10	470	76	10	2	73	< 0.01	< 10	< 10	18	< 10	120
T24618	201 238	0.02	12	360	76	5	2	68	< 0.01	< 10	< 10	18	10	122
T24619	201 238	0.01	17	910	38	5	6	22	0.02	< 10	< 10	27	10	118
T24620	201 238	0.01	19	850	60	5	4	24	0.02	< 10	< 10	28	< 10	134
T24621	201 238	0.02	17	790	58	5	3	31	0.02	< 10	< 10	30	10	160
T24622	201 238	0.01	23	1260	68	5	5	24	0.04	< 10	< 10	42	10	172
T24623	201 238	0.01	19	2200	86	< 5	5	21	0.05	< 10	< 10	55	10	698
T24624	201 238	0.01	39	1330	148	< 5	10	21	0.05	< 10	< 10	56	10	876
T24625	203 238	0.01	25	1570	18	< 5	4	19	0.03	< 10	< 10	43	< 10	210
T24626	201 238	0.01	20	950	40	< 5	4	11	0.05	< 10	< 10	59	< 10	278
T24627	201 238	0.01	18	550	16	< 5	4	11	0.06	< 10	< 10	60	< 10	98
T24628	201 238	0.01	30	1170	74	< 5	8	28	0.03	< 10	< 10	41	< 10	198
T24629	201 238	0.01	23	780	44	5	6	53	0.01	< 10	< 10	25	10	124
T24630	201 238	0.01	37	1110	48	< 5	7	28	0.04	< 10	< 10	44	< 10	218
T24631	201 238	0.01	38	460	4130	20	6	31	0.01	< 10	< 10	23	20	6830
T24632	201 238	0.01	22	560	136	10	4	36	0.01	< 10	< 10	16	10	222
T24671	201 238	0.01	18	400	586	10	4	71	< 0.01	< 10	< 10	9	10	3490
T24672	201 238	0.01	22	370	1750	15	5	57	0.01	< 10	< 10	12	< 10	2280
T24673	201 238	0.01	33	480	96	5	6	33	0.03	< 10	< 10	28	10	502
T24674	201 238	0.02	23	120	84	5	3	43	0.01	< 10	< 10	14	10	308
T24675	201 238	0.01	23	1060	96	10	4	43	< 0.01	< 10	< 10	29	< 10	166
T24676	201 238	0.02	22	850	78	5	5	41	0.02	< 10	< 10	32	< 10	168
T24677	201 238	0.01	19	900	28	< 5	3	15	0.03	< 10	< 10	43	< 10	198
T24678	201 238	0.01	30	710	32	< 5	2	12	0.03	< 10	< 10	46	< 10	196
T24679	201 238	0.01	39	1010	86	< 5	3	14	0.02	< 10	< 10	46	< 10	454
T24680	201 238	0.01	30	1610	52	< 5	6	24	0.02	< 10	< 10	42	< 10	202
T24681	201 238	0.01	24	1400	64	< 5	7	24	0.02	< 10	< 10	37	< 10	216
T24682	201 238	0.01	24	1240	60	< 5	6	14	0.03	< 10	< 10	45	< 10	246

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T24683	201 238	0.88	0.2	30	120	0.5	< 2	7.02	< 0.5	14	16	36	3.49	< 10	< 1	0.09	< 10	4.23	1255	4
T24684	201 238	1.06	0.4	20	210	0.5	4	4.93	< 0.5	15	21	46	3.61	< 10	< 1	0.07	< 10	3.14	1515	2
T24685	201 238	1.20	0.8	5	430	1.0	< 2	1.30	1.0	17	19	51	4.86	< 10	< 1	0.10	30	0.71	2110	3
T24686	201 238	0.62	1.4	25	480	< 0.5	< 2	8.15	2.5	16	15	25	3.40	< 10	< 1	0.08	< 10	4.80	2780	5
T24687	201 238	0.41	< 0.2	50	230	< 0.5	< 2	12.75	< 0.5	7	12	18	2.30	< 10	< 1	0.05	< 10	7.62	1905	4
T24688	201 238	0.30	< 0.2	40	140	< 0.5	< 2	14.35	< 0.5	5	13	12	2.16	< 10	< 1	0.05	< 10	8.61	1480	4
T25165	201 238	1.87	0.4	< 5	200	0.5	4	0.42	0.5	12	31	20	4.57	< 10	< 1	0.05	20	0.60	1620	1
T25166	201 238	1.54	0.8	< 5	110	< 0.5	< 2	0.54	0.5	15	30	45	6.10	< 10	< 1	0.12	20	0.49	2480	< 1
T25167	201 238	1.62	0.6	10	120	0.5	< 2	0.31	< 0.5	13	26	44	6.44	< 10	< 1	0.09	20	0.42	2310	1
T25168	201 238	1.62	0.2	5	130	< 0.5	< 2	0.08	< 0.5	16	24	26	4.57	< 10	< 1	0.05	20	0.41	1740	4
T25169	201 238	1.61	0.2	10	110	< 0.5	< 2	0.57	< 0.5	16	24	61	6.68	< 10	< 1	0.07	20	0.50	1695	1
T25170	217 238	0.58	< 0.2	< 5	50	< 0.5	< 2	0.64	< 0.5	14	17	24	2.87	< 10	< 1	0.23	20	0.47	1395	< 1
T25171	203 238	0.75	0.2	15	130	0.5	< 2	0.47	< 0.5	26	16	56	6.24	< 10	< 1	0.13	20	0.24	5040	2
T25172	203 238	0.75	0.6	5	90	< 0.5	< 2	0.49	< 0.5	23	21	58	7.26	< 10	< 1	0.14	20	0.34	5390	5
T25173	201 238	1.05	2.0	< 5	150	< 0.5	< 2	0.24	1.0	32	16	58	7.83	< 10	< 1	0.16	30	0.57	4290	< 1
T25174	201 238	0.64	1.4	15	160	< 0.5	< 2	0.32	< 0.5	33	13	73	7.20	< 10	< 1	0.10	40	0.30	4430	4
T25175	201 238	1.49	1.8	5	180	0.5	< 2	0.43	0.5	27	24	73	8.97	< 10	< 1	0.18	40	0.62	4720	< 1
T25176	217 238	0.83	< 0.2	< 5	100	< 0.5	< 2	0.34	< 0.5	11	45	22	2.58	< 10	< 1	0.32	20	0.18	1600	1
T25177	201 238	1.37	0.8	25	390	< 0.5	< 2	0.43	1.0	40	23	50	9.45	< 10	< 1	0.12	30	0.30	8670	< 1
T25178	201 238	0.97	1.4	10	210	< 0.5	< 2	0.40	0.5	28	21	82	8.80	< 10	< 1	0.09	30	0.32	7030	1
T25179	201 238	2.04	0.2	< 5	190	< 0.5	< 2	0.43	0.5	8	36	11	3.50	< 10	< 1	0.05	10	0.62	480	4
T25180	201 238	1.05	1.2	5	180	< 0.5	< 2	0.69	1.0	19	19	38	6.27	< 10	< 1	0.08	30	0.45	3760	6
T25181	201 238	1.38	1.0	10	330	< 0.5	< 2	2.13	1.0	18	21	27	9.21	< 10	< 1	0.05	20	1.29	8640	2
T25182	201 238	0.82	0.4	20	80	< 0.5	< 2	0.93	0.5	5	11	11	10.25	< 10	< 1	0.03	10	0.26	3300	2
T25183	201 238	1.84	0.6	< 5	220	< 0.5	< 2	0.30	0.5	12	35	26	4.77	< 10	< 1	0.07	30	0.53	1580	1
T25184	201 238	2.16	0.2	5	210	< 0.5	2	0.28	< 0.5	11	36	21	4.80	< 10	< 1	0.07	20	0.60	1080	< 1
T25185	201 238	1.94	0.2	< 5	190	< 0.5	4	0.20	< 0.5	10	35	17	4.09	< 10	< 1	0.05	20	0.53	820	5
T25186	201 238	1.32	0.2	< 5	140	< 0.5	2	0.18	< 0.5	9	26	21	4.49	< 10	< 1	0.06	20	0.34	1405	1
T25187	201 238	1.18	1.4	5	160	< 0.5	< 2	0.31	0.5	24	23	74	8.47	< 10	< 1	0.06	20	0.35	4340	2
T25188	201 238	0.71	1.4	< 5	140	< 0.5	2	0.26	0.5	25	16	56	6.42	< 10	< 1	0.05	30	0.32	3490	2
T25189	201 238	0.89	2.0	10	220	< 0.5	< 2	0.26	0.5	42	16	122	10.60	< 10	< 1	0.07	30	0.37	6510	2
T25190	201 238	1.04	2.0	< 5	190	< 0.5	< 2	0.79	1.0	31	21	64	10.80	< 10	< 1	0.15	40	0.49	5120	< 1
T25191	201 238	0.75	2.0	5	170	< 0.5	< 2	0.75	1.0	27	18	66	10.00	< 10	< 1	0.10	40	0.49	5730	< 1
T25192	201 238	1.09	1.8	< 5	350	< 0.5	< 2	0.77	1.0	30	22	68	10.85	< 10	< 1	0.10	40	0.42	6720	< 1
T25193	203 238	0.70	1.0	< 5	190	< 0.5	< 2	1.03	1.0	19	21	29	8.01	< 10	< 1	0.12	30	0.43	4850	< 1
T25194	201 238	0.71	1.0	5	340	< 0.5	< 2	0.67	1.0	19	13	22	11.10	< 10	< 1	0.07	40	0.33	6470	< 1
T25195	201 238	1.29	0.6	10	270	< 0.5	< 2	0.61	0.5	19	29	22	7.90	< 10	< 1	0.09	30	0.51	3490	1
T25196	201 238	0.66	0.6	40	180	< 0.5	< 2	8.71	< 0.5	13	21	33	3.73	< 10	< 1	0.05	< 10	5.38	1770	6
T25197	201 238	0.66	< 0.2	20	90	< 0.5	< 2	9.40	< 0.5	7	20	18	2.26	< 10	< 1	0.04	< 10	5.79	1240	4
T25198	201 238	1.33	0.8	< 5	200	< 0.5	2	1.62	1.0	15	30	26	4.38	< 10	< 1	0.06	20	0.65	2340	3

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J 2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
,125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page No. : 3-B
Tot. : 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T24683	201 238	0.01	17	1240	98	5	4	38	0.01	< 10	< 10	25	10	222
T24684	201 238	0.01	20	730	114	10	5	28	0.02	< 10	< 10	30	10	178
T24685	201 238	0.01	23	1540	210	5	6	13	0.01	< 10	< 10	36	10	392
T24686	201 238	0.01	24	1250	568	10	3	33	< 0.01	< 10	< 10	60	10	790
T24687	201 238	0.02	15	760	110	10	3	43	< 0.01	< 10	< 10	36	10	168
T24688	201 238	0.02	17	480	116	10	3	46	< 0.01	< 10	< 10	35	10	158
T25165	201 238	0.01	25	610	76	< 5	5	12	0.04	< 10	< 10	49	< 10	204
T25166	201 238	0.01	22	1080	114	< 5	7	26	0.03	< 10	< 10	39	< 10	396
T25167	201 238	0.01	22	1110	118	< 5	7	18	0.02	< 10	< 10	40	< 10	386
T25168	201 238	0.01	23	710	54	< 5	3	7	0.02	< 10	< 10	43	< 10	128
T25169	201 238	0.01	20	1140	76	< 5	6	28	0.02	< 10	< 10	37	10	166
T25170	217 238	0.01	15	530	18	< 5	2	21	< 0.01	< 10	< 10	6	< 10	92
T25171	203 238	0.01	29	1190	42	< 5	6	28	0.01	< 10	< 10	19	< 10	142
T25172	203 238	0.01	25	910	46	< 5	7	26	0.01	< 10	< 10	19	10	182
T25173	201 238	0.01	30	730	118	< 5	7	24	0.03	< 10	< 10	21	< 10	344
T25174	201 238	0.01	31	630	102	5	7	22	0.02	< 10	< 10	19	10	308
T25175	201 238	0.01	33	1290	86	< 5	11	30	0.03	< 10	< 10	33	10	332
T25176	217 238	0.01	15	670	20	< 5	2	15	0.01	< 10	< 10	16	< 10	106
T25177	201 238	0.01	27	1860	216	< 5	7	29	0.04	< 10	< 10	43	10	434
T25178	201 238	0.01	30	1020	110	< 5	8	25	0.02	< 10	< 10	27	10	270
T25179	201 238	0.01	20	760	18	< 5	3	22	0.05	< 10	< 10	54	< 10	148
T25180	201 238	0.01	30	1520	94	< 5	7	32	0.02	< 10	< 10	34	10	278
T25181	201 238	0.01	34	970	56	< 5	11	19	0.03	< 10	< 10	47	30	274
T25182	201 238	0.01	16	2110	24	< 5	9	15	0.01	< 10	< 10	52	20	122
T25183	201 238	0.01	33	860	90	< 5	6	18	0.04	< 10	< 10	57	< 10	184
T25184	201 238	0.01	27	810	36	< 5	4	20	0.05	< 10	< 10	56	< 10	156
T25185	201 238	0.01	26	560	22	< 5	4	14	0.05	< 10	< 10	55	< 10	120
T25186	201 238	0.01	18	850	26	< 5	3	12	0.03	< 10	< 10	35	< 10	130
T25187	201 238	0.01	27	1040	56	< 5	8	23	0.02	< 10	< 10	29	< 10	296
T25188	201 238	0.01	30	510	38	< 5	6	17	0.03	< 10	< 10	19	< 10	228
T25189	201 238	0.01	39	890	128	< 5	14	25	0.03	< 10	< 10	22	10	332
T25190	201 238	0.01	35	1220	80	< 5	10	29	0.01	< 10	< 10	24	10	370
T25191	201 238	0.01	27	860	80	< 5	9	26	0.01	< 10	< 10	18	10	398
T25192	201 238	0.01	32	1440	74	< 5	10	30	0.02	< 10	< 10	24	20	296
T25193	203 238	0.01	23	1010	46	< 5	6	26	0.01	< 10	< 10	15	10	286
T25194	201 238	0.01	29	900	58	< 5	7	25	0.01	< 10	< 10	19	10	304
T25195	201 238	0.01	32	910	44	< 5	7	30	0.03	< 10	< 10	34	< 10	208
T25196	201 238	0.01	23	1020	170	10	4	40	< 0.01	< 10	< 10	26	20	280
T25197	201 238	0.01	17	720	60	5	4	44	0.01	< 10	< 10	36	< 10	142
T25198	201 238	0.01	20	1600	122	< 5	3	31	0.02	< 10	< 10	52	10	276

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T[illegible]RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25199	201 238	1.28	0.6	< 5	230	0.5	< 2	0.71	< 0.5	10	25	37	4.15	< 10	< 1	0.11	30	0.53	760	1
T25200	203 238	2.13	0.8	5	210	0.5	< 2	1.26	1.0	19	38	48	5.25	< 10	< 1	0.10	20	0.66	3600	1
T25311	203 238	1.04	< 0.2	< 5	150	< 0.5	< 2	1.22	< 0.5	13	18	13	4.13	< 10	< 1	0.12	20	0.53	3700	< 1
T25312	201 238	1.20	0.4	< 5	120	< 0.5	< 2	0.51	< 0.5	19	23	28	4.60	< 10	< 1	0.19	30	0.71	2510	< 1
T25313	203 238	1.02	0.2	< 5	110	< 0.5	< 2	0.83	< 0.5	18	23	24	4.17	< 10	< 1	0.19	30	0.63	2070	< 1
T25314	201 238	0.90	0.6	< 5	120	< 0.5	< 2	1.54	< 0.5	22	14	33	4.98	< 10	< 1	0.11	30	0.95	3180	< 1
T25315	201 238	0.88	0.6	< 5	140	< 0.5	< 2	1.11	0.5	22	16	38	5.53	< 10	< 1	0.05	30	0.47	4340	< 1
T25316	201 238	0.70	0.4	10	120	< 0.5	2	1.49	< 0.5	19	18	65	3.80	< 10	< 1	0.05	20	0.48	2900	< 1
T25317	201 238	1.62	0.2	5	270	< 0.5	< 2	0.86	< 0.5	22	21	12	3.84	< 10	< 1	0.23	20	1.16	2980	< 1
T25318	201 238	0.80	0.4	< 5	210	< 0.5	< 2	1.19	< 0.5	32	9	25	6.58	< 10	< 1	0.16	30	0.50	3940	< 1
T25319	201 238	1.33	0.2	< 5	200	< 0.5	2	1.17	< 0.5	20	17	9	5.15	< 10	< 1	0.30	30	1.10	4110	< 1
T25320	201 238	1.28	0.2	< 5	130	< 0.5	< 2	1.34	0.5	19	17	10	6.06	< 10	< 1	0.17	30	0.93	4620	2
T25321	201 238	0.75	0.4	10	140	< 0.5	< 2	1.36	< 0.5	26	15	33	4.70	< 10	< 1	0.13	30	0.99	3870	< 1
T25322	201 238	0.96	0.4	< 5	120	< 0.5	2	1.54	0.5	23	18	34	4.44	< 10	< 1	0.15	30	1.23	3090	< 1
T25323	203 238	1.09	0.4	< 5	260	< 0.5	< 2	0.42	0.5	17	18	13	5.33	< 10	< 1	0.13	20	0.27	3960	< 1
T25324	201 238	1.30	1.0	10	110	< 0.5	< 2	0.58	< 0.5	36	30	87	6.56	< 10	< 1	0.12	30	0.83	3160	4
T25325	201 238	1.22	1.0	15	90	< 0.5	2	0.91	< 0.5	26	19	57	4.66	< 10	< 1	0.11	30	0.89	1950	< 1
T25326	201 238	1.03	0.8	5	110	< 0.5	< 2	1.04	0.5	14	16	45	4.84	< 10	< 1	0.07	30	0.39	3090	< 1
T25327	201 238	0.82	1.0	30	110	< 0.5	2	1.56	0.5	49	14	127	4.31	< 10	< 1	0.11	30	1.00	2770	1
T25328	201 238	0.73	< 0.2	5	170	< 0.5	< 2	1.10	< 0.5	20	8	23	4.31	< 10	< 1	0.05	10	0.27	4630	< 1
T25329	201 238	1.52	0.6	5	80	< 0.5	2	0.71	< 0.5	29	16	58	6.10	< 10	< 1	0.16	30	1.29	2380	5
T25330	201 238	1.15	0.8	5	130	< 0.5	< 2	1.45	0.5	35	21	88	5.01	< 10	< 1	0.14	40	1.19	2580	1
T25331	201 238	1.08	0.6	40	130	< 0.5	< 2	0.51	< 0.5	123	18	152	4.59	< 10	< 1	0.08	30	0.56	2340	2
T25332	201 238	1.18	1.0	5	100	< 0.5	< 2	0.41	< 0.5	38	22	83	6.49	< 10	< 1	0.08	30	0.61	2790	2
T25333	201 238	2.08	0.8	< 5	140	< 0.5	< 2	0.52	0.5	36	32	57	7.57	< 10	< 1	0.10	20	1.40	2600	< 1
T25334	201 238	0.62	0.4	10	130	< 0.5	< 2	0.31	< 0.5	16	8	11	3.77	< 10	< 1	0.10	30	0.47	3930	< 1
T25335	201 238	1.09	0.8	25	260	< 0.5	< 2	0.86	0.5	44	23	49	6.44	< 10	< 1	0.10	30	0.51	5950	2
T25336	201 238	0.79	0.6	< 5	130	< 0.5	< 2	0.69	0.5	17	16	53	5.40	< 10	< 1	0.07	30	0.33	3860	1
T25337	201 238	0.53	0.2	25	60	< 0.5	2	4.26	< 0.5	19	10	42	4.55	< 10	< 1	0.10	< 10	2.43	2780	< 1
T25338	201 238	0.44	0.4	15	50	< 0.5	4	4.22	< 0.5	16	12	48	3.51	< 10	< 1	0.07	< 10	2.43	2520	< 1
T25339	201 238	1.79	1.2	10	60	< 0.5	< 2	0.76	0.5	26	24	69	5.57	< 10	< 1	0.09	30	1.78	1830	7
T25340	201 238	0.82	0.6	< 5	90	< 0.5	< 2	0.49	0.5	15	13	29	5.10	< 10	< 1	0.08	20	0.73	3750	< 1
T25341	201 238	2.11	0.6	15	60	< 0.5	< 2	0.96	< 0.5	13	33	47	4.93	< 10	< 1	0.23	30	2.19	1465	< 1
T25342	201 238	0.87	0.8	15	80	< 0.5	< 2	0.38	< 0.5	14	16	46	3.46	< 10	< 1	0.06	30	0.34	1185	1
T25343	201 238	0.93	0.8	20	70	< 0.5	2	0.83	< 0.5	16	16	82	4.49	< 10	< 1	0.22	30	0.77	1645	2
T25344	201 238	0.85	0.8	5	140	< 0.5	< 2	1.04	< 0.5	17	12	52	5.74	< 10	< 1	0.14	30	0.45	4000	< 1
T25345	201 238	1.22	0.8	< 5	80	< 0.5	2	0.57	0.5	18	20	70	5.44	< 10	< 1	0.20	30	0.99	1990	1
T25346	201 238	0.91	0.8	5	100	< 0.5	< 2	0.50	0.5	14	17	49	5.02	< 10	< 1	0.10	30	0.45	2330	2
T25347	201 238	0.45	0.4	15	50	< 0.5	< 2	3.47	< 0.5	27	7	79	3.56	< 10	< 1	0.08	10	2.06	2660	< 1
T25348	201 238	0.24	0.6	10	50	< 0.5	< 2	1.34	< 0.5	15	5	58	3.99	< 10	< 1	0.06	20	0.67	3490	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25199	201 238	0.01	20	1110	52	< 5	6	15	0.02	< 10	< 10	29	< 10	186
T25200	203 238	0.01	30	2240	100	< 5	3	32	0.02	< 10	< 10	43	< 10	352
T25311	203 238	0.01	14	1930	28	< 5	4	13	0.01	< 10	< 10	17	< 10	84
T25312	201 238	0.01	28	850	50	< 5	5	10	0.03	< 10	< 10	28	< 10	110
T25313	203 238	0.01	24	1170	40	< 5	5	11	0.02	< 10	< 10	25	< 10	92
T25314	201 238	0.01	30	1030	36	< 5	5	14	0.02	< 10	< 10	21	< 10	172
T25315	201 238	0.01	24	1260	6	< 5	4	11	0.01	< 10	< 10	24	< 10	144
T25316	201 238	0.01	20	1250	20	< 5	3	15	0.01	< 10	< 10	20	< 10	110
T25317	201 238	0.01	36	1210	12	< 5	5	15	0.03	< 10	< 10	26	< 10	96
T25318	201 238	0.01	29	1800	4	< 5	6	23	0.01	< 10	< 10	24	< 10	72
T25319	201 238	0.01	27	1390	4	< 5	5	14	0.02	< 10	< 10	17	< 10	110
T25320	201 238	0.01	26	1800	14	< 5	4	12	0.02	< 10	< 10	20	< 10	120
T25321	201 238	0.01	26	1060	56	< 5	5	14	0.03	< 10	< 10	23	< 10	120
T25322	201 238	0.01	25	1090	28	< 5	5	16	0.04	< 10	< 10	29	< 10	108
T25323	203 238	0.01	13	2470	14	< 5	3	9	0.01	< 10	< 10	33	< 10	82
T25324	201 238	0.01	42	1110	50	< 5	9	14	0.03	< 10	< 10	50	< 10	156
T25325	201 238	0.01	35	1020	128	< 5	6	12	0.05	< 10	< 10	42	< 10	306
T25326	201 238	0.01	17	1720	170	< 5	4	11	0.02	< 10	< 10	23	< 10	276
T25327	201 238	0.01	44	1050	150	5	6	12	0.03	< 10	< 10	25	< 10	560
T25328	201 238	0.01	8	2240	94	5	3	10	0.01	< 10	< 10	21	< 10	208
T25329	201 238	0.01	35	1020	54	< 5	9	14	0.04	< 10	< 10	57	< 10	272
T25330	201 238	0.01	31	1190	62	< 5	7	19	0.05	< 10	< 10	37	< 10	136
T25331	201 238	0.01	53	960	92	< 5	6	17	0.05	< 10	< 10	36	< 10	88
T25332	201 238	0.01	43	920	46	< 5	10	12	0.02	< 10	< 10	44	10	122
T25333	201 238	0.01	36	1070	94	< 5	15	12	0.03	< 10	< 10	119	< 10	186
T25334	201 238	0.01	20	620	10	< 5	4	9	< 0.01	< 10	< 10	15	< 10	52
T25335	201 238	0.01	47	1550	46	5	5	21	0.01	< 10	< 10	29	< 10	106
T25336	201 238	0.01	29	1070	46	< 5	5	15	0.01	< 10	< 10	24	< 10	120
T25337	201 238	0.01	21	790	26	5	5	38	0.01	< 10	< 10	15	10	108
T25338	201 238	0.01	22	730	18	5	5	31	0.01	< 10	< 10	12	< 10	96
T25339	201 238	0.01	24	770	230	< 5	8	9	0.05	< 10	< 10	65	10	554
T25340	201 238	0.01	21	720	70	< 5	5	7	0.01	< 10	< 10	28	< 10	216
T25341	201 238	0.01	40	1130	50	< 5	7	15	0.03	< 10	< 10	42	< 10	316
T25342	201 238	0.01	22	910	94	5	5	12	0.03	< 10	< 10	32	< 10	180
T25343	201 238	0.01	27	880	62	5	5	11	0.02	< 10	< 10	24	< 10	272
T25344	201 238	0.01	24	1840	78	< 5	4	13	0.01	< 10	< 10	19	< 10	152
T25345	201 238	0.01	32	1050	84	< 5	6	10	0.02	< 10	< 10	24	< 10	166
T25346	201 238	0.01	26	1240	64	< 5	5	11	0.02	< 10	< 10	21	< 10	146
T25347	201 238	0.01	25	760	18	5	4	25	0.01	< 10	< 10	9	< 10	66
T25348	201 238	0.01	15	950	< 2	< 5	4	17	< 0.01	< 10	< 10	6	< 10	38

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 5-A
Tot. s: 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25349	201	238	1.00	0.6	10	90	< 0.5	< 2	0.57	< 0.5	13	19	43	4.55	< 10	< 1	0.09	20	0.50	1190	< 1
T25350	201	238	1.16	0.6	20	80	< 0.5	2	0.89	< 0.5	17	17	47	4.26	< 10	< 1	0.15	20	0.88	1035	1
T25351	201	238	1.03	0.6	10	60	< 0.5	< 2	0.53	< 0.5	15	18	50	3.23	< 10	< 1	0.08	20	0.73	595	1
T25352	201	238	0.87	0.6	15	90	< 0.5	< 2	0.60	0.5	14	17	48	4.55	< 10	< 1	0.10	20	0.46	1920	1
T25353	201	238	0.86	1.0	20	100	< 0.5	2	0.70	2.5	23	15	102	4.94	< 10	< 1	0.11	20	0.66	2520	1
T25354	201	238	1.43	0.4	20	100	0.5	2	0.50	< 0.5	16	25	44	3.73	< 10	< 1	0.21	20	1.07	1050	1
T25355	201	238	2.64	0.4	10	90	0.5	4	0.76	< 0.5	17	30	48	4.58	< 10	2	0.19	20	3.19	1450	< 1
T25356	201	238	2.98	0.2	15	60	< 0.5	4	0.41	1.5	51	31	81	10.40	< 10	< 1	0.15	20	1.75	3760	1
T25357	201	238	1.73	0.6	30	50	< 0.5	2	0.36	0.5	23	31	100	4.14	< 10	< 1	0.04	10	2.52	1780	< 1
T25358	201	238	0.54	0.2	15	90	< 0.5	< 2	1.03	< 0.5	14	11	31	3.70	< 10	< 1	0.06	10	0.44	2480	1
T25359	201	238	0.76	0.2	5	120	< 0.5	< 2	0.65	< 0.5	14	16	40	3.95	< 10	< 1	0.05	20	0.32	2220	2
T25360	201	238	0.77	0.4	10	150	< 0.5	2	0.88	< 0.5	15	14	425	3.99	< 10	< 1	0.08	20	0.33	3010	< 1
T25361	201	238	0.49	0.2	10	130	< 0.5	< 2	0.81	< 0.5	9	10	18	6.45	< 10	< 1	0.03	20	0.21	4900	< 1
T25362	201	238	0.57	0.2	15	80	< 0.5	< 2	0.89	< 0.5	10	13	37	3.32	< 10	< 1	0.05	20	0.61	1735	< 1
T25363	201	238	1.68	0.4	15	120	< 0.5	4	0.98	< 0.5	21	24	65	5.62	< 10	< 1	0.09	10	2.05	4040	< 1
T25364	201	238	2.84	1.6	45	180	< 0.5	2	0.30	1.5	67	45	645	9.80	< 10	< 1	0.11	10	2.17	5620	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 5-B
Tot. : 5
Date : 7-AUG-89
Invoice # : I-8921654
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921654

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25349	201 238	0.01	21	1000	26	< 5	6	13	0.03	< 10	< 10	25	< 10	178
T25350	201 238	0.01	24	1180	48	5	5	15	0.02	< 10	< 10	22	< 10	340
T25351	201 238	0.01	21	760	44	< 5	4	9	0.02	< 10	< 10	22	< 10	288
T25352	201 238	0.01	25	890	156	< 5	5	11	0.02	< 10	< 10	22	< 10	850
T25353	201 238	0.01	29	840	110	< 5	5	12	0.02	< 10	< 10	20	< 10	2400
T25354	201 238	0.01	29	760	42	< 5	5	15	0.04	< 10	< 10	30	< 10	352
T25355	201 238	0.01	26	1030	38	< 5	7	10	0.02	< 10	< 10	43	< 10	308
T25356	201 238	0.01	43	1340	124	< 5	22	16	0.02	< 10	< 10	156	< 10	1250
T25357	201 238	0.01	20	690	62	< 5	7	6	0.01	< 10	< 10	30	< 10	1385
T25358	201 238	0.01	15	790	12	< 5	4	10	0.01	< 10	< 10	13	< 10	124
T25359	201 238	0.01	22	900	20	< 5	5	13	0.02	< 10	< 10	20	< 10	108
T25360	201 238	0.01	18	1150	16	< 5	4	11	0.01	< 10	< 10	18	< 10	112
T25361	201 238	< 0.01	16	1070	38	< 5	4	19	< 0.01	< 10	< 10	7	< 10	166
T25362	201 238	0.01	19	810	30	< 5	4	15	0.02	< 10	< 10	17	< 10	100
T25363	201 238	0.01	27	790	66	< 5	8	16	0.02	< 10	< 10	36	< 10	174
T25364	201 238	0.01	114	1040	140	5	25	10	0.03	< 10	< 10	115	< 10	1290

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

F. ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments :

Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25367	201 238	1.87	1.0	20	90	< 0.5	2	0.05	< 0.5	28	28	53	7.21	< 10	< 1	0.13	10	0.32	3690	3
T25368	201 238	2.04	0.2	10	110	< 0.5	2	0.05	< 0.5	27	28	47	6.54	< 10	< 1	0.10	10	0.34	3100	2
T25369	201 238	2.59	< 0.2	10	150	1.0	< 2	0.06	< 0.5	39	32	48	7.28	< 10	< 1	0.13	10	0.67	4510	1
T25370	201 238	2.00	< 0.2	5	140	0.5	< 2	0.12	< 0.5	34	29	79	6.18	< 10	< 1	0.11	20	0.64	3510	1
T25371	201 238	1.86	< 0.2	10	130	1.0	< 2	0.09	< 0.5	29	24	83	5.62	< 10	< 1	0.09	20	0.64	3050	< 1
T25372	201 238	1.76	< 0.2	5	100	< 0.5	< 2	0.08	< 0.5	31	24	59	6.32	< 10	< 1	0.15	20	0.59	3140	1
T25373	201 238	1.78	< 0.2	15	100	< 0.5	2	0.09	< 0.5	22	26	57	4.82	< 10	< 1	0.12	20	0.51	2070	1
T25374	201 238	1.88	< 0.2	15	60	< 0.5	2	0.06	< 0.5	17	26	33	4.90	< 10	< 1	0.09	10	0.44	1605	1
T25375	201 238	2.10	< 0.2	15	80	< 0.5	< 2	0.03	< 0.5	27	26	38	5.60	< 10	2	0.15	20	0.83	2500	1
T25376	201 238	2.45	< 0.2	25	90	0.5	2	0.08	< 0.5	38	27	95	6.22	< 10	< 1	0.09	10	0.81	3430	1
T25377	201 238	1.96	< 0.2	< 5	80	< 0.5	< 2	0.07	0.5	22	27	39	5.32	< 10	< 1	0.08	10	0.44	2260	1
T25378	201 238	1.91	< 0.2	15	100	0.5	2	0.10	< 0.5	29	24	58	5.09	< 10	< 1	0.09	20	0.65	2550	2
T25379	201 238	0.65	0.8	55	150	< 0.5	6	6.61	< 0.5	27	11	205	7.57	< 10	< 1	0.08	< 10	3.95	5430	2
T25380	201 238	0.37	1.0	70	80	< 0.5	2	13.25	1.0	23	6	25	6.21	< 10	< 1	0.04	< 10	7.77	5040	1
T25381	201 238	0.40	0.2	35	90	< 0.5	2	10.90	< 0.5	30	9	65	6.00	< 10	< 1	0.10	< 10	6.40	4990	< 1
T25382	201 238	0.25	0.6	35	70	< 0.5	4	14.30	< 0.5	23	4	9	4.52	< 10	< 1	0.06	< 10	8.34	3570	< 1
T25383	201 238	0.67	0.6	25	210	< 0.5	2	3.84	< 0.5	97	18	13	7.70	< 10	< 1	0.20	< 10	2.38	2810	< 1
T25384	201 238	0.22	0.6	55	260	< 0.5	4	10.75	0.5	118	6	24	6.56	< 10	< 1	0.06	< 10	6.16	5030	1
T25385	201 238	0.30	0.6	5	70	< 0.5	< 2	10.45	0.5	36	9	12	5.02	< 10	< 1	0.09	< 10	5.87	4530	< 1
T25386	201 238	0.28	0.4	< 5	60	< 0.5	2	14.60	< 0.5	10	3	8	4.61	< 10	< 1	0.02	< 10	8.32	4750	< 1
T25387	201 238	1.14	0.6	< 5	240	< 0.5	< 2	6.42	0.5	14	17	22	8.42	< 10	< 1	0.04	< 10	3.86	8760	< 1
T25388	201 238	0.62	< 0.2	< 5	170	< 0.5	< 2	7.85	1.0	18	12	24	6.38	< 10	< 1	0.03	< 10	4.40	7450	< 1
T25389	201 238	0.35	0.6	< 5	60	0.5	< 2	8.60	0.5	18	8	21	3.66	< 10	< 1	0.05	< 10	4.98	2300	< 1
T25390	201 238	0.23	0.6	5	50	< 0.5	< 2	13.20	< 0.5	11	5	22	3.02	< 10	< 1	0.03	< 10	7.67	2700	< 1
T25391	201 238	0.40	0.4	5	80	< 0.5	2	9.08	< 0.5	14	7	26	3.38	< 10	< 1	0.05	< 10	5.43	2570	< 1
T25392	201 238	0.27	0.6	< 5	70	< 0.5	< 2	10.65	0.5	10	6	10	3.13	< 10	< 1	0.04	< 10	6.25	2990	< 1
T25393	201 238	0.39	0.4	< 5	90	< 0.5	2	10.50	< 0.5	12	8	18	3.72	< 10	< 1	0.04	< 10	6.28	3300	< 1
T25394	201 238	0.32	0.6	< 5	80	< 0.5	< 2	10.45	0.5	12	5	13	3.70	< 10	< 1	0.05	< 10	6.05	2810	< 1
T25395	201 238	1.15	0.6	15	110	1.0	< 2	0.94	< 0.5	14	16	19	7.34	< 10	< 1	0.12	30	0.77	3120	< 1
T25396	201 238	0.83	< 0.2	10	80	0.5	< 2	1.33	< 0.5	16	14	22	5.37	< 10	< 1	0.07	20	0.71	2160	< 1
T25397	201 238	0.44	0.6	15	60	< 0.5	< 2	8.45	0.5	13	8	20	3.66	< 10	< 1	0.04	< 10	5.11	2210	< 1
T25398	201 238	1.34	0.4	10	120	< 0.5	< 2	1.00	< 0.5	11	23	18	5.68	< 10	< 1	0.06	20	0.51	2030	< 1
T25399	201 238	0.46	1.0	20	80	< 0.5	4	8.61	0.5	11	10	17	3.45	< 10	< 1	0.06	< 10	5.26	2560	< 1
T25400	201 238	0.65	0.8	15	100	< 0.5	< 2	7.11	1.0	13	11	19	4.08	< 10	< 1	0.07	< 10	4.31	2840	< 1
T25401	201 238	0.57	0.8	10	90	< 0.5	< 2	7.98	0.5	12	11	17	3.55	< 10	< 1	0.06	< 10	4.87	2440	< 1
T25402	201 238	0.44	0.6	5	60	< 0.5	< 2	0.88	< 0.5	6	9	16	3.08	< 10	< 1	0.04	10	0.33	1560	< 1
T25403	201 238	0.42	0.6	10	80	< 0.5	< 2	2.21	< 0.5	11	8	26	4.21	< 10	< 1	0.06	< 10	1.20	2940	< 1
T25404	201 238	0.61	1.2	< 5	110	< 0.5	< 2	2.52	0.5	13	12	33	5.75	< 10	< 1	0.04	< 10	1.31	4250	< 1
T25405	201 238	0.89	1.0	10	140	< 0.5	< 2	1.21	1.5	16	14	34	4.84	< 10	< 1	0.06	10	0.43	3430	< 1
T25406	201 238	1.33	0.4	5	220	< 0.5	< 2	1.38	1.0	12	21	22	4.33	< 10	< 1	0.05	10	0.55	4610	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 1-B
Tot. Pages: 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25367	201 238	0.01	23	2060	24	< 5	1	6	0.01	< 10	< 10	43	< 10	194
T25368	201 238	0.01	20	2110	20	< 5	1	6	0.01	< 10	< 10	43	< 10	186
T25369	201 238	0.01	24	2430	32	< 5	2	7	0.02	< 10	< 10	41	< 10	172
T25370	201 238	0.01	30	1110	32	< 5	3	11	0.03	< 10	< 10	39	< 10	166
T25371	201 238	0.01	34	620	28	< 5	3	10	0.03	< 10	< 10	33	< 10	164
T25372	201 238	0.01	24	1290	20	< 5	1	7	0.01	< 10	< 10	30	< 10	130
T25373	201 238	0.01	23	830	20	< 5	2	9	0.03	< 10	< 10	40	< 10	142
T25374	201 238	0.01	18	1370	14	< 5	1	7	0.02	< 10	< 10	39	< 10	112
T25375	201 238	0.01	26	850	24	< 5	3	5	0.01	< 10	< 10	31	< 10	192
T25376	201 238	0.01	41	670	32	< 5	4	10	0.02	< 10	< 10	31	< 10	272
T25377	201 238	0.01	19	820	24	< 5	2	7	0.02	< 10	< 10	42	< 10	134
T25378	201 238	0.01	34	800	36	< 5	3	14	0.02	< 10	< 10	30	< 10	198
T25379	201 238	0.01	28	720	28	5	4	14	0.01	< 10	< 10	15	10	178
T25380	201 238	0.01	24	420	62	10	3	17	0.01	< 10	< 10	9	20	204
T25381	201 238	0.01	29	690	38	5	11	23	< 0.01	< 10	< 10	18	10	120
T25382	201 238	0.02	18	430	14	5	4	13	< 0.01	< 10	< 10	8	10	80
T25383	201 238	0.01	67	1980	30	5	19	16	< 0.01	< 10	< 10	30	10	110
T25384	201 238	0.01	52	840	50	5	9	24	< 0.01	< 10	< 10	21	10	194
T25385	201 238	0.01	36	1180	124	5	11	47	< 0.01	< 10	< 10	23	10	274
T25386	201 238	0.02	13	270	6	5	6	62	0.01	< 10	< 10	9	10	126
T25387	201 238	0.01	24	790	14	5	5	26	0.02	< 10	< 10	24	20	216
T25388	201 238	0.01	23	1190	14	5	6	27	0.01	< 10	< 10	25	10	470
T25389	201 238	0.01	20	540	46	5	5	19	0.01	< 10	< 10	12	10	256
T25390	201 238	0.02	10	300	24	5	4	21	< 0.01	< 10	< 10	9	10	126
T25391	201 238	0.01	16	420	14	5	4	18	0.01	< 10	< 10	13	10	138
T25392	201 238	0.01	12	390	26	5	4	21	< 0.01	< 10	< 10	9	10	192
T25393	201 238	0.01	14	400	22	5	4	26	0.01	< 10	< 10	13	10	232
T25394	201 238	0.01	13	460	16	5	5	27	< 0.01	< 10	< 10	9	10	158
T25395	201 238	0.01	25	940	62	< 5	9	13	0.01	< 10	< 10	19	< 10	326
T25396	201 238	0.01	20	830	38	5	7	10	0.01	< 10	< 10	17	< 10	292
T25397	201 238	0.01	12	550	54	5	5	18	< 0.01	< 10	< 10	12	< 10	488
T25398	201 238	0.01	18	1290	54	< 5	6	12	0.02	< 10	< 10	36	< 10	374
T25399	201 238	0.01	15	480	50	5	5	29	0.01	< 10	< 10	15	< 10	438
T25400	201 238	0.01	17	680	54	5	5	23	0.01	< 10	< 10	18	10	548
T25401	201 238	0.02	15	480	44	< 5	5	21	0.01	< 10	< 10	18	10	402
T25402	201 238	0.01	6	710	26	< 5	4	15	< 0.01	< 10	< 10	7	< 10	186
T25403	201 238	0.01	15	720	32	< 5	4	19	< 0.01	< 10	< 10	7	< 10	216
T25404	201 238	0.01	25	920	60	5	4	16	0.01	< 10	< 10	15	< 10	376
T25405	201 238	0.01	22	1010	98	5	4	15	0.01	< 10	< 10	20	< 10	832
T25406	201 238	0.01	20	1520	46	< 5	4	21	0.02	< 10	< 10	32	< 10	356

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page No. : 2-A
Tot. Pgs. : 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25407	201 238	1.19	0.8	15	250	< 0.5	2	1.49	1.0	14	18	26	4.60	< 10	1	0.05	10	0.50	5820	< 1
T25408	201 238	1.11	1.0	20	130	< 0.5	4	1.33	< 0.5	14	23	41	5.34	< 10	< 1	0.06	10	0.82	3480	< 1
T25409	201 238	1.37	0.6	10	110	< 0.5	4	0.98	< 0.5	17	27	34	5.39	< 10	< 1	0.07	10	0.72	2500	< 1
T25410	201 238	2.26	1.0	15	100	< 0.5	2	0.61	0.5	29	49	118	6.03	< 10	< 1	0.06	20	2.56	2690	< 1
T25411	201 238	1.51	0.8	30	140	< 0.5	2	0.62	< 0.5	21	31	46	5.42	< 10	< 1	0.06	20	0.78	2690	< 1
T25412	201 238	1.35	0.4	10	120	< 0.5	< 2	0.66	< 0.5	25	21	63	6.53	< 10	1	0.10	20	0.86	3300	< 1
T25413	201 238	0.71	< 0.2	5	90	< 0.5	4	1.44	< 0.5	18	10	26	4.40	< 10	< 1	0.10	20	0.97	2890	< 1
T25414	201 238	0.69	0.4	10	80	< 0.5	2	3.15	< 0.5	20	10	23	4.41	< 10	< 1	0.11	< 10	1.95	3060	< 1
T25415	201 238	0.30	0.8	35	30	< 0.5	2	5.48	< 0.5	47	8	29	5.67	< 10	1	0.03	< 10	3.03	3520	1
T25416	203 238	1.57	0.4	15	50	< 0.5	< 2	3.20	< 0.5	41	66	78	6.44	< 10	1	0.19	< 10	2.24	3670	< 1
T25417	203 238	3.00	< 0.2	10	40	< 0.5	2	0.54	< 0.5	36	150	146	6.16	< 10	1	0.10	10	3.27	2510	< 1
T25418	203 238	4.12	0.6	10	50	< 0.5	16	0.49	1.0	57	149	280	8.44	< 10	< 1	0.05	< 10	3.56	2500	< 1
T25419	201 238	4.02	0.4	10	110	< 0.5	< 2	1.74	0.5	57	97	402	9.52	< 10	< 1	0.22	< 10	3.61	2590	< 1
T25420	203 238	3.02	0.8	30	80	< 0.5	< 2	1.63	1.5	52	125	364	7.37	< 10	< 1	0.11	< 10	3.39	2830	< 1
T25421	203 238	3.09	0.8	20	60	< 0.5	2	0.50	0.5	57	138	376	7.38	< 10	< 1	0.10	< 10	2.32	2400	< 1
T25422	203 238	4.14	0.8	5	30	< 0.5	< 2	1.77	1.0	54	164	312	8.63	< 10	< 1	0.16	< 10	4.31	2260	< 1
T25423	201 238	3.14	1.0	30	90	< 0.5	6	0.64	1.0	66	134	669	6.96	< 10	< 1	0.03	10	2.19	1950	< 1
T25424	201 238	1.15	0.6	15	40	< 0.5	< 2	7.54	< 0.5	22	16	92	4.25	< 10	< 1	0.20	< 10	5.56	2530	3
T25425	201 238	0.24	0.6	45	30	< 0.5	2	10.80	< 0.5	21	7	81	4.43	< 10	< 1	0.04	< 10	6.26	2690	< 1
T25426	201 238	3.49	0.6	45	30	< 0.5	< 2	1.38	1.5	61	74	343	5.79	< 10	< 1	0.09	10	4.74	2030	< 1
T25427	201 238	2.29	0.8	75	20	< 0.5	4	7.01	0.5	38	38	243	4.27	< 10	< 1	0.31	< 10	4.35	860	10
T25428	217 238	0.47	0.8	55	40	< 0.5	2	4.40	0.5	39	42	197	5.19	< 10	< 1	0.16	< 10	2.47	1835	14
T25429	201 238	0.32	0.8	50	40	< 0.5	4	8.87	0.5	27	6	146	4.47	< 10	< 1	0.09	< 10	5.11	2490	7
T25430	203 238	0.34	0.6	35	50	< 0.5	6	7.79	< 0.5	25	55	76	3.60	< 10	< 1	0.20	< 10	4.28	2270	7
T25431	203 238	0.72	1.2	40	90	< 0.5	14	2.56	0.5	33	52	59	7.09	< 10	< 1	0.21	10	1.24	3960	1
T25432	217 238	0.43	1.0	85	20	< 0.5	32	2.02	< 0.5	93	65	95	4.56	< 10	< 1	0.28	10	0.73	2150	26
T25433	201 238	0.19	0.8	95	50	< 0.5	6	10.50	< 0.5	40	6	48	6.69	< 10	< 1	0.05	< 10	5.77	4290	7
T25434	201 238	0.21	1.0	70	60	< 0.5	14	5.79	< 0.5	36	6	231	4.24	< 10	< 1	0.09	< 10	2.75	2030	11
T25435	201 238	0.62	1.2	55	140	< 0.5	2	4.92	< 0.5	51	14	47	7.19	< 10	< 1	0.12	< 10	3.05	4080	12
T25436	201 238	0.80	0.8	25	90	< 0.5	10	6.44	0.5	30	18	53	5.87	< 10	< 1	0.06	< 10	4.62	3570	2
T25626	201 238	1.67	0.8	< 5	240	< 0.5	4	0.84	0.5	12	26	32	4.03	< 10	< 1	0.09	20	0.70	960	< 1
T25627	201 238	1.53	0.8	5	180	< 0.5	< 2	1.24	0.5	25	22	40	4.34	< 10	< 1	0.11	10	0.52	3310	2
T25628	203 238	1.30	0.8	10	130	< 0.5	6	5.78	< 0.5	24	34	29	3.73	< 10	< 1	0.20	< 10	3.60	2150	2
T25629	201 238	0.22	1.2	10	60	< 0.5	< 2	14.70	< 0.5	12	6	11	1.59	< 10	< 1	0.04	< 10	8.90	1385	2
T25630	201 238	0.62	1.2	15	100	< 0.5	2	8.63	< 0.5	11	13	26	2.80	< 10	< 1	0.07	< 10	5.11	750	3
T25631	201 238	0.41	1.2	10	200	< 0.5	< 2	11.40	0.5	13	9	24	2.57	< 10	< 1	0.06	< 10	6.59	1395	5
T25632	201 238	0.58	1.0	25	110	< 0.5	4	10.80	< 0.5	17	10	25	2.49	< 10	< 1	0.09	< 10	6.51	1175	4
T25633	201 238	0.50	1.0	25	80	< 0.5	4	10.85	< 0.5	13	9	26	2.48	< 10	< 1	0.06	< 10	6.44	825	4
T25634	201 238	0.75	1.2	10	110	< 0.5	4	7.47	0.5	16	14	33	3.14	< 10	< 1	0.06	< 10	4.54	1150	4
T25635	201 238	0.86	1.8	15	180	< 0.5	2	0.52	0.5	36	15	88	10.70	< 10	1	0.11	40	0.50	4800	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J 2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page : 2-B
Tot. : 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25407	201 238	0.01	20	1660	52	5	3	18	0.02	< 10	< 10	26	< 10	452
T25408	201 238	0.01	26	1140	66	< 5	5	25	0.02	< 10	< 10	33	< 10	414
T25409	201 238	0.01	21	880	100	< 5	6	18	0.03	< 10	< 10	41	< 10	312
T25410	201 238	0.01	45	740	118	< 5	11	9	0.05	< 10	< 10	60	< 10	704
T25411	201 238	0.01	30	830	28	< 5	7	12	0.02	< 10	< 10	37	< 10	190
T25412	201 238	0.01	33	830	12	< 5	10	11	0.02	< 10	< 10	35	< 10	118
T25413	201 238	0.01	29	740	6	< 5	5	14	0.01	< 10	< 10	16	< 10	58
T25414	201 238	0.01	28	890	4	< 5	5	25	0.01	< 10	< 10	15	< 10	52
T25415	201 238	0.01	47	610	38	10	5	23	< 0.01	< 10	< 10	8	< 10	56
T25416	203 238	0.01	62	1220	18	5	11	32	< 0.01	< 10	< 10	51	< 10	94
T25417	203 238	0.01	76	490	42	< 5	13	8	0.12	< 10	< 10	98	< 10	248
T25418	203 238	0.01	79	250	102	< 5	14	11	0.14	< 10	< 10	145	10	422
T25419	201 238	0.01	70	470	128	< 5	23	18	0.10	< 10	< 10	230	10	440
T25420	203 238	0.02	72	620	174	< 5	12	20	0.09	< 10	< 10	104	10	1150
T25421	203 238	0.01	85	320	110	< 5	19	48	0.07	< 10	< 10	134	< 10	512
T25422	203 238	0.01	98	310	88	5	18	19	0.12	< 10	< 10	152	10	924
T25423	201 238	0.01	89	1100	318	< 5	12	57	0.07	< 10	< 10	104	< 10	830
T25424	201 238	0.01	27	840	26	< 5	7	19	0.02	< 10	< 10	12	10	98
T25425	201 238	0.01	42	580	16	10	4	16	< 0.01	< 10	< 10	12	10	140
T25426	201 238	0.01	73	550	158	< 5	9	13	0.15	< 10	< 10	88	10	892
T25427	201 238	0.01	56	1140	84	5	6	36	0.09	< 10	< 10	67	10	716
T25428	217 238	0.01	83	1340	40	20	4	30	< 0.01	< 10	< 10	19	< 10	288
T25429	201 238	0.01	61	1200	66	10	4	43	< 0.01	< 10	< 10	23	< 10	210
T25430	203 238	0.01	45	1250	26	10	4	49	< 0.01	< 10	< 10	18	< 10	38
T25431	203 238	0.01	48	1390	52	10	6	32	< 0.01	< 10	< 10	11	< 10	308
T25432	217 238	0.01	285	2380	16	25	6	33	< 0.01	< 10	< 10	9	< 10	34
T25433	201 238	0.01	70	1000	44	15	4	24	< 0.01	< 10	< 10	20	10	64
T25434	201 238	0.01	86	1280	98	10	3	32	< 0.01	< 10	< 10	10	< 10	52
T25435	201 238	0.01	106	1420	42	10	8	35	< 0.01	< 10	< 10	36	< 10	90
T25436	201 238	0.01	28	590	22	5	6	14	0.01	< 10	< 10	23	< 10	590
T25626	201 238	0.01	23	1560	60	5	6	20	0.01	< 10	< 10	31	< 10	170
T25627	201 238	0.01	18	1700	76	5	4	17	0.02	< 10	< 10	31	< 10	210
T25628	203 238	0.01	21	1260	72	5	3	24	0.01	< 10	< 10	28	< 10	196
T25629	201 238	0.02	9	640	120	5	2	47	< 0.01	< 10	< 10	24	< 10	160
T25630	201 238	0.02	11	1160	114	5	3	34	0.01	< 10	< 10	22	< 10	222
T25631	201 238	0.01	14	940	118	5	2	46	< 0.01	< 10	< 10	15	< 10	218
T25632	201 238	0.02	17	830	72	5	4	47	< 0.01	< 10	< 10	15	< 10	150
T25633	201 238	0.01	14	1020	68	5	3	47	< 0.01	< 10	< 10	15	< 10	162
T25634	201 238	0.01	20	1120	92	5	5	34	0.01	< 10	< 10	20	< 10	206
T25635	201 238	0.01	33	900	90	5	9	22	0.01	< 10	< 10	17	< 10	480

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T[illegible]RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25636	201 238	0.21	1.0	10	70	0.5	< 2	9.56	1.0	19	6	43	3.98	< 10	< 1	0.03	< 10	5.63	2520	< 1
T25637	201 238	0.25	2.8	20	90	0.5	< 2	8.84	3.0	19	7	68	3.79	< 10	< 1	0.04	< 10	5.24	2110	< 1
T25638	201 238	0.49	8.2	100	100	1.0	< 2	4.57	6.0	24	10	137	5.11	< 10	< 1	0.04	< 10	2.69	1560	< 1
T25639	201 238	0.26	5.4	55	670	0.5	< 2	7.97	2.5	23	7	209	4.44	< 10	< 1	0.03	< 10	4.79	1875	< 1
T25640	201 238	0.25	40.0	260	110	0.5	< 2	8.44	19.0	45	7	224	6.33	< 10	< 1	0.02	< 10	4.99	1490	2
T25641	201 238	0.37	12.6	55	120	0.5	< 2	8.64	6.5	21	12	131	3.70	< 10	< 1	0.04	< 10	5.15	1695	< 1
T25642	201 238	0.34	9.0	80	290	0.5	< 2	8.66	7.5	29	9	145	4.17	< 10	< 1	0.02	< 10	5.17	1785	1
T25643	201 238	0.22	40.5	110	60	0.5	< 2	8.41	25.5	37	6	192	4.64	< 10	< 1	0.03	< 10	5.14	1655	< 1
T25691	201 238	0.55	0.8	10	70	0.5	< 2	3.59	< 0.5	17	11	33	4.98	< 10	< 1	0.07	< 10	2.25	3350	< 1
T25692	201 238	0.35	0.4	5	90	0.5	< 2	3.02	< 0.5	14	6	44	6.04	< 10	< 1	0.04	< 10	1.61	5340	< 1
T25693	201 238	2.19	0.6	15	100	1.0	< 2	0.45	1.0	52	30	66	11.00	< 10	< 1	0.20	10	1.35	3100	< 1
T25694	201 238	1.50	0.6	10	140	1.0	< 2	1.65	0.5	14	19	34	5.09	< 10	< 1	0.18	10	1.88	4090	< 1
T25695	201 238	3.58	0.4	5	100	1.5	< 2	1.13	1.0	29	44	37	5.53	< 10	< 1	0.11	20	4.38	1365	< 1
T25696	201 238	3.15	0.6	15	60	1.0	< 2	1.82	< 0.5	14	31	55	3.57	< 10	1	0.04	< 10	4.44	1040	< 1
T25697	201 238	0.63	0.6	10	100	1.0	< 2	1.39	1.0	16	12	41	4.79	< 10	< 1	0.09	20	0.84	3140	< 1
T25698	201 238	0.64	0.8	5	70	1.0	< 2	0.88	0.5	12	10	38	5.97	< 10	< 1	0.12	20	0.46	2820	< 1
T25699	201 238	0.40	0.6	< 5	50	0.5	< 2	1.11	< 0.5	10	12	28	5.90	< 10	< 1	0.04	10	0.30	2170	< 1
T25700	201 238	0.58	0.6	< 5	80	1.0	< 2	0.96	0.5	12	11	41	4.94	< 10	< 1	0.06	20	0.40	2110	< 1
T25701	201 238	0.70	0.6	10	90	1.0	< 2	0.56	< 0.5	13	14	41	4.68	< 10	1	0.06	20	0.34	2130	< 1
T25702	201 238	0.66	0.6	10	90	0.5	< 2	1.42	< 0.5	14	10	74	4.74	< 10	1	0.07	10	0.48	3170	< 1
T25751	201 238	1.62	0.8	< 5	150	1.0	< 2	2.57	1.0	11	28	20	2.79	< 10	< 1	0.09	< 10	1.63	1175	12
T25752	201 238	0.16	0.4	< 5	30	< 0.5	< 2	>15.00	< 0.5	6	2	4	0.47	< 10	< 1	0.01	< 10	11.50	465	3
T25753	201 238	0.34	0.6	< 5	50	< 0.5	< 2	>15.00	0.5	7	7	8	0.99	< 10	< 1	0.03	< 10	10.20	805	4
T25754	201 238	0.20	0.6	< 5	40	< 0.5	< 2	>15.00	0.5	7	3	6	0.73	< 10	< 1	0.01	< 10	11.05	695	4
T25755	201 238	0.26	0.8	5	90	< 0.5	< 2	14.90	0.5	7	5	19	1.15	< 10	< 1	0.01	< 10	9.16	870	5
T25756	201 238	0.66	0.8	< 5	160	0.5	< 2	13.20	1.0	9	12	22	2.05	< 10	< 1	0.03	< 10	8.06	1650	9
T25757	201 238	0.27	0.8	< 5	60	< 0.5	< 2	>15.00	1.0	7	4	6	0.78	< 10	1	0.02	< 10	9.65	820	6
T25758	201 238	0.25	0.6	< 5	180	< 0.5	< 2	>15.00	1.0	7	5	8	0.94	< 10	< 1	0.02	< 10	9.71	735	2
T25759	201 238	0.50	0.4	< 5	180	0.5	< 2	13.80	1.0	8	9	12	1.22	< 10	< 1	0.02	< 10	8.34	1350	2
T25760	201 238	0.58	0.8	< 5	100	0.5	< 2	13.90	1.5	9	15	11	1.46	< 10	< 1	0.02	< 10	8.40	1850	3
T25761	201 238	0.54	1.0	< 5	80	2.0	< 2	1.20	0.5	16	8	26	5.93	< 10	< 1	0.07	20	0.73	2770	< 1
T25762	201 238	0.68	0.6	< 5	100	1.5	< 2	4.40	0.5	18	14	26	5.02	< 10	< 1	0.04	< 10	2.64	2370	< 1
T25776	201 238	0.13	0.4	10	20	< 0.5	< 2	>15.00	< 0.5	6	3	3	0.40	< 10	< 1	< 0.01	< 10	11.20	390	< 1
T25777	201 238	0.26	0.4	< 5	50	< 0.5	< 2	>15.00	< 0.5	6	5	4	0.64	< 10	< 1	0.01	< 10	10.55	630	< 1
T25778	201 238	0.38	0.4	< 5	50	< 0.5	< 2	>15.00	< 0.5	7	10	7	0.95	< 10	< 1	0.02	< 10	9.90	420	2
T25779	201 238	0.21	1.0	20	30	< 0.5	< 2	>15.00	< 0.5	9	6	21	2.30	< 10	< 1	0.02	< 10	9.98	635	23
T25780	201 238	0.37	1.0	25	50	< 0.5	< 2	14.65	0.5	17	13	14	1.80	< 10	< 1	0.02	< 10	8.69	1910	4
T25781	201 238	0.13	0.8	5	30	< 0.5	< 2	>15.00	0.5	14	7	21	1.67	< 10	< 1	< 0.01	< 10	10.55	1845	1
T25782	201 238	0.13	0.6	< 5	110	< 0.5	< 2	>15.00	1.0	32	7	33	2.03	< 10	< 1	0.01	< 10	10.15	5160	1
T25783	201 238	0.63	0.6	< 5	60	< 0.5	< 2	14.30	0.5	13	12	14	1.64	< 10	< 1	0.02	< 10	8.87	1785	< 1

CERTIFICATION :

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

F RCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 3-B
Tot. : 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25636	201 238	0.01	22	350	72	10	4	54	< 0.01	< 10	< 10	6	10	590
T25637	201 238	0.01	20	400	1505	10	4	26	< 0.01	< 10	< 10	8	10	1415
T25638	201 238	0.01	37	680	4110	20	5	16	0.01	< 10	< 10	14	< 10	4540
T25639	201 238	0.01	26	430	2980	20	4	49	< 0.01	< 10	< 10	8	< 10	1640
T25640	201 238	0.01	53	460	>10000	80	4	25	< 0.01	< 10	< 10	7	20	>10000
T25641	201 238	0.01	29	490	4530	25	4	29	0.01	< 10	< 10	11	10	5390
T25642	201 238	0.01	29	480	3040	20	4	49	0.01	< 10	< 10	11	10	6250
T25643	201 238	0.01	39	380	>10000	15	4	34	< 0.01	< 10	< 10	9	30	>10000
T25691	201 238	0.01	20	620	88	< 5	7	14	< 0.01	< 10	< 10	16	< 10	272
T25692	201 238	0.01	18	760	38	5	8	24	< 0.01	< 10	< 10	8	< 10	130
T25693	201 238	0.01	56	1090	174	< 5	25	10	0.04	< 10	< 10	152	< 10	812
T25694	201 238	0.01	21	1280	30	< 5	5	14	0.03	< 10	< 10	31	< 10	388
T25695	201 238	0.01	25	940	110	< 5	12	17	0.15	< 10	< 10	102	< 10	1570
T25696	201 238	0.01	20	1200	64	< 5	6	25	0.04	< 10	< 10	56	< 10	564
T25697	201 238	0.01	23	850	50	5	5	18	0.02	< 10	< 10	17	< 10	688
T25698	201 238	0.01	21	1100	38	< 5	6	12	0.01	< 10	< 10	11	< 10	460
T25699	201 238	0.01	13	940	60	5	4	15	< 0.01	< 10	< 10	13	< 10	208
T25700	201 238	0.01	18	970	26	< 5	5	16	0.01	< 10	< 10	13	< 10	248
T25701	201 238	0.01	22	890	26	< 5	6	17	0.02	< 10	< 10	20	< 10	208
T25702	201 238	0.01	16	1350	14	5	4	19	0.01	< 10	< 10	10	< 10	98
T25751	201 238	0.01	27	1320	60	< 5	3	16	0.03	< 10	< 10	85	< 10	400
T25752	201 238	0.02	3	400	24	5	< 1	39	< 0.01	< 10	< 10	9	< 10	108
T25753	201 238	0.02	7	860	108	5	1	37	< 0.01	< 10	< 10	14	< 10	248
T25754	201 238	0.02	4	430	32	5	< 1	42	< 0.01	< 10	< 10	7	< 10	94
T25755	201 238	0.02	8	610	74	5	1	34	< 0.01	< 10	< 10	9	< 10	170
T25756	201 238	0.02	14	1070	138	5	1	32	0.01	< 10	< 10	19	< 10	262
T25757	201 238	0.02	4	540	64	5	< 1	34	< 0.01	< 10	< 10	10	< 10	244
T25758	201 238	0.02	8	640	118	5	1	52	< 0.01	< 10	< 10	8	< 10	224
T25759	201 238	0.02	7	1040	78	5	1	41	0.01	< 10	< 10	13	< 10	266
T25760	201 238	0.02	11	1100	98	5	1	45	0.01	< 10	< 10	17	< 10	298
T25761	201 238	0.01	23	580	98	5	6	22	< 0.01	< 10	< 10	13	< 10	232
T25762	201 238	0.01	22	1060	104	5	7	40	0.01	< 10	< 10	34	< 10	244
T25776	201 238	0.02	2	320	< 2	5	< 1	28	< 0.01	< 10	< 10	4	< 10	24
T25777	201 238	0.02	3	540	2	5	< 1	29	< 0.01	< 10	< 10	6	< 10	44
T25778	201 238	0.02	8	410	2	5	1	46	0.01	< 10	< 10	12	< 10	52
T25779	201 238	0.02	16	450	40	5	1	57	< 0.01	< 10	< 10	20	< 10	112
T25780	201 238	0.02	15	780	248	5	2	56	0.01	< 10	< 10	30	< 10	310
T25781	201 238	0.02	14	590	82	< 5	1	65	< 0.01	< 10	< 10	53	< 10	336
T25782	201 238	0.02	24	810	44	5	1	66	< 0.01	< 10	< 10	86	< 10	598
T25783	201 238	0.02	13	1010	12	< 5	1	33	0.01	< 10	< 10	49	< 10	202

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

[illegible]RCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Page [illegible] 4-A
Tot. [illegible] 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25784	201 238	0.39	3.4	15	50	0.5	2	8.92	< 0.5	16	15	134	2.58	< 10	< 1	0.04	< 10	5.32	1465	< 1
T25785	201 238	0.54	0.8	< 5	310	0.5	< 2	7.74	0.5	21	22	37	5.91	< 10	< 1	0.03	< 10	4.50	4010	< 1
T25786	201 238	0.59	0.6	< 5	190	1.5	2	8.39	0.5	25	22	18	7.30	< 10	1	0.04	< 10	4.92	5160	< 1
T25787	201 238	0.45	0.4	< 5	110	0.5	< 2	10.55	0.5	18	14	22	4.68	< 10	< 1	0.03	< 10	6.25	2700	< 1
T25788	201 238	0.29	0.8	5	40	0.5	2	9.35	0.5	15	7	17	3.87	< 10	< 1	0.03	< 10	5.34	1990	< 1
T25789	201 238	0.63	0.8	5	100	0.5	< 2	0.35	< 0.5	3	10	11	1.92	< 10	< 1	0.11	10	0.14	360	< 1
T25790	201 238	0.74	1.4	25	100	2.5	< 2	0.59	1.0	25	11	36	12.35	< 10	< 1	0.05	10	0.43	5610	< 1
T25791	201 238	0.59	0.2	5	70	1.0	< 2	0.63	< 0.5	8	9	16	3.39	< 10	< 1	0.07	10	0.20	760	< 1
T25792	201 238	0.14	< 0.2	< 5	130	< 0.5	< 2	>15.00	< 0.5	6	2	22	0.98	< 10	< 1	< 0.01	< 10	10.80	950	< 1
T25793	201 238	0.47	< 0.2	< 5	60	0.5	< 2	>15.00	0.5	7	10	7	1.01	< 10	< 1	0.03	< 10	9.34	735	2
T25794	201 238	0.21	< 0.2	< 5	50	< 0.5	< 2	>15.00	1.0	6	4	4	0.70	< 10	< 1	0.01	< 10	10.30	820	< 1
T25795	201 238	0.29	< 0.2	< 5	50	< 0.5	< 2	>15.00	0.5	6	4	5	1.21	< 10	< 1	0.02	< 10	9.66	500	2
T25796	201 238	0.80	0.2	< 5	80	0.5	< 2	11.15	0.5	9	14	9	1.35	< 10	< 1	0.04	< 10	6.82	1010	3
T25797	201 238	0.69	0.6	< 5	80	0.5	< 2	13.05	2.0	8	13	11	1.50	< 10	< 1	0.05	< 10	8.08	1185	5
T25798	201 238	0.42	< 0.2	10	60	< 0.5	< 2	14.25	< 0.5	7	8	13	1.03	< 10	< 1	0.02	< 10	8.83	905	5
T25799	201 238	0.47	0.2	< 5	60	0.5	< 2	14.90	0.5	9	11	13	1.48	< 10	< 1	0.04	< 10	8.97	950	5
T25800	201 238	0.31	0.8	45	90	0.5	< 2	>15.00	0.5	10	10	19	2.38	< 10	< 1	0.04	< 10	8.75	835	15
T25801	201 238	0.79	0.6	10	270	1.0	4	5.85	0.5	14	17	33	3.41	< 10	1	0.06	< 10	3.53	1500	3
T25802	201 238	1.02	0.6	10	210	1.0	4	5.68	0.5	18	21	31	4.02	< 10	< 1	0.07	< 10	3.45	2440	6
T25803	201 238	0.94	0.8	< 5	260	1.0	< 2	5.09	1.0	17	22	23	3.80	< 10	< 1	0.07	< 10	2.97	2360	3
T25804	201 238	1.56	1.2	15	390	1.5	4	2.15	1.5	14	30	29	4.32	< 10	1	0.08	10	1.17	3650	10
T25805	201 238	0.70	0.8	5	290	0.5	< 2	13.45	1.0	12	10	22	2.00	< 10	< 1	0.05	< 10	8.03	2080	8
T25806	201 238	0.51	< 0.2	< 5	90	< 0.5	< 2	14.20	0.5	6	9	9	1.13	< 10	< 1	0.03	< 10	8.63	895	2
T25807	201 238	1.87	0.8	5	220	1.5	4	1.83	1.0	12	31	22	3.32	< 10	< 1	0.10	10	1.03	2500	2
T25808	201 238	0.58	< 0.2	< 5	80	0.5	< 2	14.55	0.5	8	10	10	1.46	< 10	< 1	0.02	< 10	9.05	1050	< 1
T25809	201 238	1.23	1.4	< 5	130	1.0	< 2	0.41	< 0.5	9	21	45	3.47	< 10	< 1	0.13	30	0.39	870	5
T25810	201 238	0.67	0.4	< 5	110	1.0	< 2	5.25	0.5	17	16	24	4.49	< 10	< 1	0.04	< 10	3.19	2530	< 1
T25811	201 238	1.14	0.4	< 5	160	1.5	2	0.94	0.5	17	21	25	5.92	< 10	< 1	0.06	20	0.47	2900	< 1
T25812	201 238	1.04	0.4	15	90	1.0	< 2	0.08	< 0.5	11	17	21	4.29	< 10	< 1	0.08	10	0.26	1155	< 1
T25813	201 238	0.85	0.8	5	140	1.0	2	5.70	0.5	25	22	26	6.50	< 10	< 1	0.03	< 10	3.44	4430	< 1
T25814	201 238	1.01	1.2	< 5	100	1.5	< 2	0.97	1.0	15	19	27	5.44	< 10	< 1	0.05	20	0.62	1890	< 1
T25815	201 238	1.48	1.0	5	190	1.0	< 2	1.07	0.5	21	33	23	7.80	< 10	< 1	0.05	20	0.59	3770	< 1
T25816	201 238	0.51	3.4	25	90	0.5	< 2	7.60	0.5	27	13	40	3.93	< 10	< 1	0.04	< 10	4.42	1685	1
T25817	201 238	0.90	0.8	10	220	0.5	< 2	1.91	0.5	18	24	21	4.44	< 10	< 1	0.06	< 10	0.98	3330	< 1
T25818	201 238	1.28	0.4	< 5	130	0.5	< 2	5.42	0.5	15	24	21	2.71	< 10	< 1	0.03	< 10	3.56	1620	< 1
T25819	201 238	0.98	0.4	5	110	0.5	< 2	11.10	1.0	22	18	24	2.46	< 10	< 1	0.02	< 10	6.94	2630	< 1
T25820	201 238	1.21	0.6	10	120	0.5	< 2	4.98	1.5	15	22	26	3.14	< 10	< 1	0.04	< 10	3.33	1905	1
T25821	201 238	1.23	0.6	20	220	0.5	< 2	7.26	1.0	22	24	30	3.40	< 10	< 1	0.06	< 10	4.68	2260	4
T25822	201 238	1.29	0.4	5	140	0.5	< 2	4.71	0.5	10	24	16	2.37	< 10	< 1	0.06	< 10	3.17	945	9
T25823	201 238	0.65	< 0.2	10	70	< 0.5	< 2	12.30	< 0.5	7	12	9	1.54	< 10	< 1	0.03	< 10	7.79	640	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25784	201 238	0.02	15	890	214	5	4	43	0.01	< 10	< 10	77	< 10	230
T25785	201 238	0.01	22	1400	106	5	5	56	0.02	< 10	< 10	73	< 10	216
T25786	201 238	0.01	23	1190	160	5	5	60	0.02	< 10	< 10	99	10	290
T25787	201 238	0.02	14	1000	158	5	4	101	0.01	< 10	< 10	54	< 10	196
T25788	201 238	0.02	16	350	250	5	4	55	< 0.01	< 10	< 10	12	< 10	290
T25789	201 238	0.01	8	720	42	< 5	2	12	< 0.01	< 10	< 10	19	< 10	68
T25790	201 238	0.01	37	740	170	5	13	19	< 0.01	< 10	< 10	17	< 10	540
T25791	201 238	0.01	12	850	42	< 5	3	19	< 0.01	< 10	< 10	19	< 10	124
T25792	201 238	0.02	2	500	94	5	< 1	88	< 0.01	< 10	< 10	4	< 10	124
T25793	201 238	0.02	8	1400	98	5	1	54	0.01	< 10	< 10	11	< 10	266
T25794	201 238	0.02	4	630	42	5	< 1	66	< 0.01	< 10	< 10	5	< 10	166
T25795	201 238	0.02	5	740	40	5	1	30	< 0.01	< 10	< 10	8	< 10	110
T25796	201 238	0.02	9	920	44	5	1	25	0.02	< 10	< 10	20	< 10	164
T25797	201 238	0.02	11	860	314	5	2	35	0.01	< 10	< 10	21	< 10	746
T25798	201 238	0.02	8	620	64	5	2	39	0.01	< 10	< 10	12	< 10	210
T25799	201 238	0.02	10	770	58	5	2	58	< 0.01	< 10	< 10	15	< 10	130
T25800	201 238	0.02	20	750	136	5	2	70	< 0.01	< 10	< 10	19	< 10	324
T25801	201 238	0.01	18	1000	102	5	4	26	0.01	< 10	< 10	26	< 10	204
T25802	201 238	0.01	27	1180	112	5	5	27	0.01	< 10	< 10	35	< 10	282
T25803	201 238	0.01	23	1160	114	5	4	25	0.01	< 10	< 10	31	< 10	288
T25804	201 238	0.01	26	1600	196	5	3	16	0.02	< 10	< 10	46	< 10	488
T25805	201 238	0.02	17	1340	122	5	2	53	0.01	< 10	< 10	33	< 10	276
T25806	201 238	0.02	8	700	46	5	1	39	0.01	< 10	< 10	13	< 10	174
T25807	201 238	0.01	23	2030	210	< 5	2	18	0.03	< 10	< 10	47	< 10	472
T25808	201 238	0.02	9	610	38	5	1	59	0.01	< 10	< 10	17	< 10	140
T25809	201 238	0.01	18	600	52	< 5	5	20	0.02	< 10	< 10	38	< 10	108
T25810	201 238	0.01	16	900	88	5	6	49	0.01	< 10	< 10	47	< 10	210
T25811	201 238	0.01	20	1310	74	5	6	23	0.01	< 10	< 10	49	< 10	212
T25812	201 238	0.01	16	380	82	< 5	2	12	0.01	< 10	< 10	39	< 10	152
T25813	201 238	0.01	23	1350	164	5	6	50	0.02	< 10	< 10	92	< 10	280
T25814	201 238	0.01	25	820	190	< 5	6	15	0.02	< 10	< 10	40	< 10	300
T25815	201 238	0.01	23	1240	114	< 5	6	23	0.03	< 10	< 10	121	< 10	272
T25816	201 238	0.01	28	980	628	10	4	58	0.01	< 10	< 10	57	< 10	190
T25817	201 238	0.01	23	1320	110	< 5	3	19	0.01	< 10	< 10	144	< 10	248
T25818	201 238	0.02	22	1060	42	5	3	24	0.03	< 10	< 10	69	< 10	214
T25819	201 238	0.01	27	1330	72	5	2	29	0.01	< 10	< 10	76	< 10	450
T25820	201 238	0.01	31	880	118	< 5	3	19	0.03	< 10	< 10	66	< 10	554
T25821	201 238	0.02	30	910	152	5	4	38	0.04	< 10	< 10	67	< 10	530
T25822	201 238	0.02	25	810	18	5	3	27	0.04	< 10	< 10	42	< 10	122
T25823	201 238	0.02	10	560	14	5	1	27	0.02	< 10	< 10	20	< 10	90

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

RCHER CATHRO & ASSOC. (1981) LTD

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 5-A
Tot. Pages: 5
Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T25824	201 238	0.51	< 0.2	< 5	70	< 0.5	< 2	12.60	< 0.5	8	10	8	1.22	< 10	< 1	0.02	< 10	7.69	495	< 1
T25825	201 238	0.28	< 0.2	< 5	80	< 0.5	< 2	14.25	< 0.5	22	21	25	2.96	< 10	< 1	0.07	< 10	8.42	385	1
T25838	201 238	1.17	< 0.2	< 5	90	9.0	< 2	0.38	1.0	37	13	124	>15.00	< 10	< 1	0.06	< 10	0.33	1680	< 1
T25839	201 238	1.21	0.6	10	100	2.0	< 2	0.16	< 0.5	17	18	34	6.04	< 10	1	0.07	10	0.24	1265	1
T25840	201 238	1.04	1.6	15	160	2.0	< 2	7.14	1.0	28	14	39	5.86	< 10	1	0.05	< 10	4.28	4570	< 1
T25841	201 238	0.39	< 0.2	< 5	70	< 0.5	< 2	>15.00	< 0.5	10	5	9	1.95	< 10	< 1	0.01	< 10	9.77	1660	< 1
T25842	201 238	0.35	< 0.2	10	100	< 0.5	< 2	>15.00	< 0.5	13	5	11	2.10	< 10	< 1	0.01	< 10	9.77	2320	< 1
T25843	201 238	0.40	0.2	< 5	180	0.5	< 2	14.90	0.5	13	6	20	2.50	< 10	< 1	0.01	< 10	9.16	2860	< 1
T25844	201 238	1.12	2.0	15	180	1.0	2	6.81	1.0	15	23	38	4.38	< 10	< 1	0.06	< 10	4.07	1860	4
T25845	201 238	0.47	0.4	25	110	0.5	< 2	13.30	0.5	13	12	17	2.47	< 10	< 1	0.03	< 10	7.95	1415	7
T25846	201 238	0.91	0.6	15	150	1.5	< 2	0.72	< 0.5	14	18	15	4.65	< 10	< 1	0.04	20	0.45	1615	< 1
T25847	201 238	0.81	0.6	5	230	1.0	< 2	0.67	< 0.5	13	19	46	4.46	< 10	1	0.07	20	0.38	990	< 1
T25848	201 238	0.91	0.4	10	220	1.0	< 2	1.39	< 0.5	11	16	31	3.99	< 10	< 1	0.07	10	0.41	1225	< 1
T25849	201 238	1.45	0.2	20	320	1.0	< 2	0.74	< 0.5	8	25	32	4.36	< 10	< 1	0.15	30	0.51	580	< 1
T25850	201 238	2.30	1.4	10	200	1.5	2	0.96	0.5	40	26	47	4.76	< 10	1	0.15	20	0.79	5370	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 8-AUG-89
Invoice # : I-8921655
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8921655

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T25824	201 238	0.02	8	1130	8	5	1	31	0.01	< 10	< 10	16	< 10	56
T25825	201 238	0.01	42	2370	16	10	8	85	< 0.01	< 10	< 10	23	10	18
T25838	201 238	0.01	60	820	158	5	18	15	< 0.01	< 10	< 10	14	< 10	620
T25839	201 238	0.01	34	870	286	< 5	3	10	0.01	< 10	< 10	39	< 10	332
T25840	201 238	0.01	42	1970	196	5	4	24	0.01	< 10	< 10	35	< 10	582
T25841	201 238	0.01	5	1110	74	< 5	1	20	< 0.01	< 10	< 10	19	< 10	134
T25842	201 238	0.01	11	940	56	5	1	23	< 0.01	< 10	< 10	22	< 10	186
T25843	201 238	0.01	11	670	86	5	1	26	0.01	< 10	< 10	21	< 10	234
T25844	201 238	0.01	27	1820	180	5	4	32	0.01	< 10	< 10	43	< 10	320
T25845	201 238	0.02	19	660	90	5	3	60	< 0.01	< 10	< 10	17	< 10	200
T25846	201 238	0.01	21	960	54	5	6	10	0.01	< 10	< 10	25	< 10	124
T25847	201 238	0.01	23	970	48	< 5	9	11	0.02	< 10	< 10	24	< 10	126
T25848	201 238	0.01	15	1510	102	< 5	4	16	0.01	< 10	< 10	20	< 10	126
T25849	201 238	0.01	22	1330	50	< 5	6	17	0.02	< 10	< 10	29	< 10	142
T25850	201 238	0.01	30	1520	126	< 5	7	24	0.03	< 10	< 10	33	< 10	328

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-A
Tot. Pages: 6
Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 21972	203	238	0.66	8.0	55	100	< 0.5	4	6.93	13.0	36	14	211	4.16	< 10	2	0.10	< 10	4.40	1865	< 1
T 21973	201	238	0.76	9.0	50	110	< 0.5	8	6.11	12.5	53	16	339	4.67	< 10	1	0.12	< 10	3.97	2080	< 1
T 21974	201	238	0.25	< 0.2	10	70	< 0.5	4	8.53	4.0	23	2	110	3.18	< 10	< 1	0.08	< 10	4.80	2440	< 1
T 21975	201	238	0.22	41.2	615	90	< 0.5	10	7.36	27.5	121	3	1025	6.56	< 10	5	0.03	< 10	4.41	1365	< 1
T 21976	201	238	0.38	4.4	25	60	< 0.5	6	3.42	7.5	42	5	374	3.64	< 10	2	0.10	< 10	1.92	2260	< 1
T 21977	203	238	0.35	1.2	15	90	< 0.5	6	2.79	0.5	33	4	159	4.16	< 10	< 1	0.10	< 10	1.58	2630	< 1
T 21978	201	238	0.55	1.2	45	120	0.5	4	2.05	< 0.5	41	9	177	4.65	< 10	< 1	0.12	20	1.27	2460	< 1
T 21979	201	238	1.24	2.0	25	200	< 0.5	8	0.74	2.5	258	35	694	8.17	< 10	< 1	0.09	10	1.05	4010	< 1
T 21980	201	238	1.13	1.0	< 5	180	< 0.5	10	0.41	2.0	73	26	321	8.83	< 10	< 1	0.09	20	0.61	4310	< 1
T 21985	201	238	0.54	19.0	70	40	< 0.5	4	7.37	5.5	31	8	184	4.13	< 10	< 1	0.05	< 10	4.57	1635	< 1
T 21986	201	238	0.43	61.4	140	210	< 0.5	12	6.56	20.0	51	6	291	6.45	< 10	1	0.04	< 10	4.00	2290	< 1
T 21987	201	238	0.35	78.4	285	490	< 0.5	14	5.88	48.0	83	5	544	7.79	< 10	5	0.04	< 10	3.61	1685	< 1
T 21988	201	238	0.30	56.2	410	130	< 0.5	10	6.51	36.5	85	3	414	7.83	< 10	< 1	0.05	< 10	3.94	2440	< 1
T 21989	201	238	0.26	62.4	580	180	< 0.5	16	5.68	57.0	99	2	443	10.50	< 10	< 1	0.05	< 10	3.41	2110	< 1
T 23571	201	238	0.24	36.2	565	50	< 0.5	18	1.35	2.0	47	3	118	>15.00	< 10	3	0.02	10	0.98	5700	< 1
T 23572	201	238	0.36	4.2	155	110	< 0.5	10	7.98	5.0	64	4	84	9.53	< 10	< 1	0.05	< 10	5.04	5670	< 1
T 23573	201	238	0.45	12.0	50	50	< 0.5	2	10.85	20.5	23	6	122	4.90	< 10	< 1	0.05	< 10	6.07	3130	< 1
T 23574	201	238	0.53	3.0	30	50	< 0.5	4	1.25	1.0	17	8	22	3.73	< 10	< 1	0.15	30	0.74	765	< 1
T 23575	201	238	0.57	20.8	65	50	< 0.5	2	4.33	4.0	24	10	64	5.24	< 10	3	0.11	< 10	2.69	630	< 1
T 23576	201	238	0.95	9.6	55	60	0.5	8	5.23	20.0	29	15	60	3.83	< 10	2	0.07	< 10	3.36	2220	< 1
T 23577	201	238	0.63	31.0	220	50	< 0.5	16	2.68	74.5	51	12	127	9.82	< 10	24	0.09	< 10	1.67	810	< 1
T 23578	201	238	0.60	1.6	25	90	0.5	8	2.03	1.5	43	10	35	6.10	< 10	< 1	0.17	20	1.13	1190	< 1
T 23579	201	238	0.12	32.0	185	40	< 0.5	10	11.85	10.5	28	2	1005	10.60	< 10	1	0.02	< 10	6.78	5190	< 1
T 23580	201	238	0.19	14.4	525	50	< 0.5	22	7.90	4.5	31	2	546	>15.00	20	20	0.01	< 10	4.84	2110	< 1
T 23581	201	238	0.15	73.2	265	10	< 0.5	16	8.13	58.0	34	2	171	8.20	< 10	13	0.02	< 10	5.12	2050	< 1
T 23582	201	238	0.24	36.0	225	< 10	< 0.5	14	8.84	56.5	34	2	101	5.87	< 10	1	0.01	< 10	5.57	1100	< 1
T 23583	201	238	0.35	4.0	65	50	< 0.5	12	8.63	5.0	36	3	35	7.72	< 10	< 1	0.05	< 10	5.05	3700	< 1
T 23584	201	238	0.37	< 0.2	115	60	< 0.5	10	10.50	1.5	21	4	36	8.01	< 10	< 1	0.04	< 10	6.28	3820	< 1
T 23585	201	238	0.45	3.4	55	70	0.5	8	6.72	0.5	35	8	82	4.57	< 10	< 1	0.06	< 10	3.63	2130	< 1
T 23586	201	238	0.21	147.0	185	10	< 0.5	10	12.60	52.5	45	3	276	3.73	< 10	< 1	0.04	< 10	7.66	1135	< 1
T 23587	201	238	0.18	20.0	160	20	< 0.5	6	10.40	24.0	42	3	147	6.20	< 10	< 1	0.05	< 10	6.39	1830	< 1
T 23588	201	238	0.19	4.8	120	10	< 0.5	4	11.30	15.5	41	4	77	4.56	< 10	1	0.05	< 10	6.93	1935	< 1
T 23589	201	238	0.15	16.2	155	10	< 0.5	12	8.24	37.5	39	4	110	5.51	< 10	2	0.04	< 10	5.07	1800	< 1
T 23590	201	238	0.45	1.0	10	70	< 0.5	2	4.31	1.5	22	8	61	4.09	< 10	< 1	0.07	< 10	2.57	2020	< 1
T 23591	201	238	0.64	3.0	45	80	< 0.5	6	3.01	1.0	34	12	210	5.79	< 10	2	0.08	< 10	1.81	2050	< 1
T 23592	201	238	0.51	1.8	60	80	< 0.5	6	2.78	0.5	35	9	59	5.30	< 10	< 1	0.06	< 10	1.66	1620	< 1
T 23593	201	238	0.19	84.8	110	10	< 0.5	4	10.60	27.0	34	4	316	2.69	< 10	2	0.03	< 10	6.60	1080	< 1
T 23594	201	238	0.14	51.2	155	10	< 0.5	8	9.30	32.0	39	3	195	4.58	< 10	< 1	0.03	< 10	5.69	1700	< 1
T 23595	201	238	0.71	8.4	55	80	< 0.5	8	0.80	5.5	52	13	130	8.56	< 10	< 1	0.13	40	0.58	3190	< 1
T 23596	201	238	0.24	23.0	160	20	< 0.5	10	7.33	19.5	49	4	173	5.52	< 10	< 1	0.07	< 10	4.53	1945	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page No. : 1-B
Tot. Pages: 6
Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 21972	203	238	0.01	40	480	6140	15	8	36	< 0.01	< 10	< 10	35	30	>10000
T 21973	201	238	0.01	55	580	4800	20	9	31	< 0.01	< 10	< 10	42	20	>10000
T 21974	201	238	0.01	16	470	432	15	5	76	< 0.01	< 10	< 10	10	10	4070
T 21975	201	238	0.01	85	480	>10000	125	3	65	< 0.01	< 10	< 10	9	50	>10000
T 21976	201	238	0.01	29	730	2060	20	6	60	< 0.01	< 10	< 10	14	10	6080
T 21977	203	238	0.01	23	800	194	15	7	53	< 0.01	< 10	< 10	11	10	322
T 21978	201	238	0.01	31	850	154	10	7	48	0.01	< 10	< 10	15	< 10	266
T 21979	201	238	0.01	233	520	704	5	20	13	< 0.01	< 10	< 10	86	10	4130
T 21980	201	238	0.01	75	540	200	10	24	18	0.01	< 10	< 10	74	10	3030
T 21985	201	238	0.01	31	530	7450	45	5	25	0.02	< 10	< 10	19	10	6960
T 21986	201	238	0.01	59	520	>10000	130	5	37	0.01	< 10	< 10	14	50	>10000
T 21987	201	238	0.01	101	420	>10000	160	5	36	0.01	< 10	< 10	12	70	>10000
T 21988	201	238	0.01	89	490	>10000	85	5	49	< 0.01	< 10	< 10	13	60	>10000
T 21989	201	238	0.01	120	480	>10000	90	5	63	< 0.01	< 10	< 10	13	80	>10000
T 23571	201	238	< 0.01	175	< 10	1650	150	4	5	< 0.01	60	< 10	8	20	5010
T 23572	201	238	0.01	82	280	4890	65	4	11	< 0.01	< 10	< 10	13	30	6990
T 23573	201	238	0.01	30	330	>10000	30	3	26	0.02	< 10	< 10	20	30	>10000
T 23574	201	238	0.01	21	680	1180	15	8	10	0.01	< 10	< 10	15	< 10	1650
T 23575	201	238	0.01	48	570	>10000	115	7	27	0.02	< 10	< 10	18	20	9390
T 23576	201	238	0.02	35	620	>10000	25	4	21	0.05	< 10	< 10	32	30	>10000
T 23577	201	238	0.01	78	530	>10000	30	6	16	0.02	< 10	< 10	21	60	>10000
T 23578	201	238	0.01	33	870	426	10	9	15	0.01	< 10	< 10	16	10	976
T 23579	201	238	0.01	62	50	>10000	495	5	15	< 0.01	10	< 10	16	40	5810
T 23580	201	238	0.01	82	20	2240	160	3	12	< 0.01	10	< 10	10	60	9860
T 23581	201	238	0.01	43	170	>10000	140	2	11	< 0.01	< 10	< 10	7	70	>10000
T 23582	201	238	0.01	58	210	>10000	30	3	12	< 0.01	< 10	< 10	7	60	>10000
T 23583	201	238	0.01	52	250	1030	20	3	25	< 0.01	< 10	< 10	7	30	4700
T 23584	201	238	0.01	39	310	630	25	3	24	0.01	< 10	< 10	12	20	1150
T 23585	201	238	0.01	42	1380	264	40	3	32	0.01	< 10	< 10	15	10	542
T 23586	201	238	0.02	41	310	>10000	225	2	21	< 0.01	< 10	< 10	7	80	>10000
T 23587	201	238	0.01	51	230	>10000	60	3	19	< 0.01	< 10	< 10	8	40	>10000
T 23588	201	238	0.02	47	330	2980	20	4	27	< 0.01	< 10	< 10	8	20	>10000
T 23589	201	238	0.01	49	280	8210	35	4	20	< 0.01	< 10	< 10	7	40	>10000
T 23590	201	238	0.01	28	630	212	15	5	18	0.01	< 10	< 10	15	10	982
T 23591	201	238	0.01	43	640	326	35	6	13	0.01	< 10	< 10	19	10	1295
T 23592	201	238	0.01	56	520	174	25	5	13	0.01	< 10	< 10	15	10	754
T 23593	201	238	0.01	28	340	>10000	155	2	21	< 0.01	< 10	< 10	7	40	>10000
T 23594	201	238	0.01	41	240	>10000	120	3	31	< 0.01	< 10	< 10	6	40	>10000
T 23595	201	238	0.01	44	620	3580	25	13	14	0.02	< 10	< 10	19	< 10	4230
T 23596	201	238	0.01	50	320	>10000	60	4	25	< 0.01	< 10	< 10	8	30	>10000

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 23597	201	238	0.23	0.4	70	40	0.5	< 2	9.23	2.0	27	3	80	5.39	< 10	< 1	0.03	< 10	5.62	1390	< 1
T 23598	201	238	0.64	1.8	60	120	< 0.5	< 2	1.40	< 0.5	46	11	98	5.77	10	< 1	0.08	30	0.87	1960	< 1
T 23599	201	238	0.33	30.0	130	10	< 0.5	2	7.17	39.0	55	4	197	4.08	< 10	< 1	0.15	< 10	4.51	1160	< 1
T 23600	201	238	0.31	62.4	170	10	< 0.5	4	9.16	42.5	56	3	186	3.48	< 10	< 1	0.09	< 10	5.66	1350	< 1
T 25644	201	238	2.09	0.4	< 5	180	< 0.5	< 2	0.87	< 0.5	11	31	22	3.54	10	< 1	0.10	10	0.60	960	< 1
T 25645	201	238	2.08	0.6	< 5	290	< 0.5	< 2	0.75	0.5	10	31	32	3.53	10	< 1	0.18	20	0.61	610	< 1
T 25646	201	238	2.13	< 0.2	5	210	< 0.5	< 2	0.49	< 0.5	33	33	29	4.78	10	< 1	0.19	10	0.49	3850	< 1
T 25647	201	238	1.91	0.4	< 5	290	< 0.5	< 2	1.35	0.5	15	27	31	3.96	10	< 1	0.14	20	0.64	2760	< 1
T 25648	201	238	2.38	0.2	< 5	230	< 0.5	< 2	1.09	< 0.5	12	33	25	3.82	10	< 1	0.14	20	0.85	1230	< 1
T 25649	201	238	1.46	0.4	< 5	280	< 0.5	< 2	0.89	0.5	19	29	35	5.52	10	5	0.10	20	0.66	2070	< 1
T 25650	201	238	1.34	0.6	5	340	< 0.5	< 2	0.92	< 0.5	7	23	24	4.10	10	< 1	0.06	20	0.51	670	< 1
T 25651	201	238	0.83	0.6	5	130	< 0.5	< 2	0.97	0.5	12	14	23	4.68	10	< 1	0.06	20	0.33	1750	< 1
T 25652	201	238	0.80	0.2	< 5	190	< 0.5	< 2	3.89	0.5	13	16	25	4.19	10	< 1	0.06	< 10	2.32	1800	< 1
T 25653	201	238	1.00	< 0.2	< 5	140	< 0.5	< 2	10.80	1.0	10	18	25	3.04	< 10	< 1	0.03	< 10	6.78	1940	< 1
T 25654	201	238	0.93	< 0.2	< 5	140	< 0.5	< 2	11.40	1.0	11	17	38	3.06	< 10	< 1	0.04	< 10	7.06	1670	< 1
T 25655	201	238	1.37	2.6	< 5	390	< 0.5	< 2	0.79	1.0	15	25	41	6.49	10	< 1	0.12	20	0.42	1760	< 1
T 25656	201	238	1.41	3.4	15	480	< 0.5	2	2.28	1.5	22	31	32	5.00	10	< 1	0.11	< 10	1.32	2130	< 1
T 25657	201	238	1.09	1.2	5	150	< 0.5	< 2	0.09	1.0	20	15	48	6.58	10	< 1	0.11	20	0.15	2400	< 1
T 25658	201	238	1.31	0.6	< 5	120	< 0.5	< 2	0.61	< 0.5	7	14	16	3.00	10	< 1	0.13	10	0.26	330	< 1
T 25659	201	238	1.42	0.8	< 5	130	< 0.5	< 2	0.17	0.5	8	22	17	3.60	10	< 1	0.10	10	0.28	895	< 1
T 25660	201	238	1.78	1.4	< 5	180	< 0.5	< 2	0.27	1.0	8	29	21	5.25	10	< 1	0.11	20	0.46	1375	< 1
T 25661	201	238	1.34	0.8	< 5	160	< 0.5	< 2	1.01	1.5	16	27	27	6.09	10	1	0.07	10	0.57	3820	< 1
T 25662	201	238	2.18	0.2	< 5	200	< 0.5	2	1.35	1.5	22	37	31	5.26	10	< 1	0.12	20	0.73	4840	< 1
T 25663	201	238	1.43	< 0.2	< 5	150	< 0.5	< 2	6.30	1.0	15	28	17	3.42	< 10	< 1	0.08	< 10	3.84	2300	< 1
T 25664	201	238	1.76	< 0.2	10	130	< 0.5	< 2	5.65	0.5	17	31	23	4.08	10	< 1	0.15	< 10	3.60	2080	< 1
T 25665	201	238	1.90	< 0.2	10	210	< 0.5	< 2	7.36	1.0	23	34	32	4.81	10	< 1	0.11	< 10	4.61	5490	5
T 25666	201	238	2.55	0.4	20	230	< 0.5	< 2	1.71	0.5	15	42	24	4.60	10	< 1	0.13	20	1.04	2370	2
T 25667	201	238	0.59	< 0.2	5	80	< 0.5	< 2	14.75	0.5	11	12	31	1.92	< 10	< 1	0.08	< 10	9.28	1015	2
T 25668	201	238	1.81	< 0.2	5	170	< 0.5	2	4.93	0.5	15	30	26	3.66	10	< 1	0.08	< 10	2.89	2890	1
T 25669	201	238	0.83	< 0.2	< 5	80	< 0.5	< 2	11.20	1.0	9	17	15	1.67	< 10	< 1	0.05	< 10	7.19	910	2
T 25670	201	238	1.76	0.2	< 5	180	< 0.5	< 2	1.42	0.5	13	33	21	4.11	10	< 1	0.09	10	0.92	1765	< 1
T 25671	201	238	0.70	< 0.2	< 5	60	< 0.5	< 2	10.95	0.5	12	15	15	2.35	< 10	< 1	0.05	< 10	6.88	1750	1
T 25672	201	238	1.17	0.4	5	140	< 0.5	< 2	3.08	0.5	18	25	27	4.26	10	< 1	0.09	< 10	1.88	2010	< 1
T 25673	201	238	1.84	0.4	10	180	< 0.5	4	2.22	1.0	19	37	33	4.25	10	< 1	0.12	< 10	1.13	3250	2
T 25674	201	238	1.83	0.8	15	180	< 0.5	< 2	1.27	0.5	17	35	31	4.05	10	< 1	0.12	20	0.80	1390	< 1
T 25675	201	238	1.79	0.4	< 5	170	< 0.5	< 2	1.32	1.0	11	31	22	3.51	10	< 1	0.12	20	0.75	1340	1
T 25676	201	238	1.31	< 0.2	10	180	< 0.5	< 2	2.89	1.0	20	26	34	3.83	10	< 1	0.10	< 10	1.64	2650	< 1
T 25677	201	238	1.69	0.6	< 5	180	< 0.5	< 2	0.70	0.5	9	32	20	4.21	10	< 1	0.11	20	0.52	1260	< 1
T 25678	201	238	1.53	1.2	< 5	150	< 0.5	< 2	0.52	1.5	15	31	23	5.47	10	< 1	0.10	20	0.52	2230	< 1
T 25679	201	238	1.42	2.4	< 5	130	< 0.5	< 2	0.57	1.5	15	25	27	6.63	10	< 1	0.10	10	0.43	2370	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 23597	201	238	0.01	38	280	242	20	4	29	< 0.01	< 10	< 10	9	10	2050
T 23598	201	238	0.01	53	630	166	20	9	14	0.02	< 10	< 10	19	< 10	528
T 23599	201	238	0.01	51	400	>10000	55	4	28	< 0.01	< 10	< 10	8	40	>10000
T 23600	201	238	0.01	42	420	>10000	80	4	34	< 0.01	< 10	< 10	9	50	>10000
T 25644	201	238	0.01	16	1230	100	< 5	3	29	0.05	< 10	< 10	64	< 10	314
T 25645	201	238	0.01	20	1580	36	< 5	5	24	0.04	< 10	< 10	45	< 10	210
T 25646	201	238	0.01	18	1810	72	< 5	3	24	0.06	< 10	< 10	63	< 10	256
T 25647	201	238	0.01	21	1850	74	< 5	5	34	0.03	< 10	< 10	41	< 10	264
T 25648	201	238	0.01	23	1920	60	< 5	6	29	0.04	< 10	< 10	44	< 10	216
T 25649	201	238	0.01	36	1080	110	5	8	15	0.03	< 10	< 10	45	< 10	262
T 25650	201	238	0.01	20	1090	58	5	6	15	0.03	< 10	< 10	36	< 10	152
T 25651	201	238	< 0.01	18	1160	58	< 5	6	13	0.01	< 10	< 10	24	< 10	272
T 25652	201	238	0.01	19	780	150	10	6	23	0.01	< 10	< 10	28	< 10	370
T 25653	201	238	0.01	17	1070	100	< 5	2	22	0.02	< 10	< 10	48	10	190
T 25654	201	238	0.02	19	1570	118	5	3	53	0.03	< 10	< 10	45	10	192
T 25655	201	238	0.01	41	1360	256	5	8	13	0.02	< 10	< 10	61	< 10	414
T 25656	201	238	0.01	40	1350	926	10	5	22	0.03	< 10	< 10	67	< 10	1040
T 25657	201	238	0.01	46	710	254	5	6	8	0.01	< 10	< 10	34	< 10	646
T 25658	201	238	0.01	14	790	60	5	3	22	0.01	< 10	< 10	30	< 10	126
T 25659	201	238	0.01	21	360	258	< 5	2	15	0.04	< 10	< 10	51	< 10	298
T 25660	201	238	0.01	26	550	362	< 5	6	19	0.05	< 10	< 10	50	< 10	468
T 25661	201	238	0.01	31	1250	362	5	5	19	0.03	< 10	< 10	82	< 10	450
T 25662	201	238	0.01	33	2210	78	< 5	6	30	0.05	< 10	< 10	138	< 10	380
T 25663	201	238	0.01	20	1470	42	5	3	26	0.03	< 10	< 10	84	10	300
T 25664	201	238	0.02	24	1400	58	5	6	41	0.04	< 10	< 10	111	10	298
T 25665	201	238	0.01	36	1820	76	5	4	35	0.04	< 10	< 10	135	10	470
T 25666	201	238	0.01	33	2050	58	5	4	26	0.05	< 10	< 10	134	< 10	366
T 25667	201	238	0.02	15	840	24	5	2	53	0.02	< 10	< 10	58	< 10	154
T 25668	201	238	0.01	23	1930	44	5	3	29	0.03	< 10	< 10	103	< 10	272
T 25669	201	238	0.01	18	750	14	5	2	36	0.03	< 10	< 10	40	< 10	116
T 25670	201	238	0.01	24	1330	42	5	4	24	0.04	< 10	< 10	85	< 10	320
T 25671	201	238	0.01	16	1040	40	5	3	46	0.01	< 10	< 10	57	< 10	178
T 25672	201	238	0.01	26	1130	426	< 5	6	41	0.04	< 10	< 10	56	< 10	306
T 25673	201	238	0.01	30	1810	284	5	4	27	0.04	< 10	< 10	100	< 10	568
T 25674	201	238	0.01	30	1220	306	5	7	32	0.05	< 10	< 10	81	< 10	696
T 25675	201	238	0.01	25	1580	80	5	4	26	0.06	< 10	< 10	73	< 10	346
T 25676	201	238	0.01	23	1480	254	5	6	28	0.03	< 10	< 10	67	< 10	652
T 25677	201	238	0.01	26	1180	166	5	5	22	0.05	< 10	< 10	63	< 10	302
T 25678	201	238	0.01	31	700	402	< 5	6	22	0.05	< 10	< 10	52	< 10	356
T 25679	201	238	0.01	28	920	746	5	6	18	0.03	< 10	< 10	50	< 10	752

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 3-A
Tot. Pages: 6
Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 25680	201	238	2.11	0.2	< 5	240	< 0.5	< 2	0.48	0.5	15	34	19	5.29	10	< 1	0.08	10	0.54	2440	1
T 25681	201	238	2.32	0.8	30	310	0.5	< 2	0.79	< 0.5	15	34	19	4.86	10	< 1	0.12	20	0.63	2060	< 1
T 25682	201	238	1.08	< 0.2	< 5	280	< 0.5	< 2	7.53	1.0	16	19	54	3.86	< 10	< 1	0.06	< 10	4.79	2170	< 1
T 25683	201	238	1.51	0.4	< 5	150	0.5	< 2	1.54	1.0	9	26	18	3.01	10	< 1	0.09	10	0.71	885	2
T 25684	201	238	1.67	0.8	15	260	0.5	< 2	0.88	1.5	19	32	23	6.29	10	< 1	0.08	20	0.42	3800	< 1
T 25685	201	238	1.76	1.4	5	330	0.5	< 2	0.83	1.0	17	33	37	5.32	10	< 1	0.12	20	0.57	2190	< 1
T 25686	201	238	2.36	0.8	< 5	240	< 0.5	< 2	0.60	0.5	11	40	22	4.72	10	< 1	0.13	20	0.64	965	< 1
T 25687	201	238	2.23	0.6	25	260	0.5	< 2	1.18	1.0	16	38	23	5.17	10	< 1	0.14	30	0.75	2770	1
T 25688	201	238	1.62	1.4	< 5	250	< 0.5	< 2	0.95	1.5	17	27	26	6.46	20	< 1	0.10	20	0.53	3580	< 1
T 25689	201	238	1.96	0.8	< 5	180	0.5	< 2	1.43	1.0	14	32	23	4.68	10	< 1	0.13	20	0.88	1690	< 1
T 25690	201	238	2.29	0.6	25	220	0.5	< 2	0.93	< 0.5	12	33	20	4.78	10	< 1	0.14	20	0.76	1820	1
T 25703	201	238	0.98	< 0.2	5	110	0.5	< 2	2.38	< 0.5	11	16	33	1.66	< 10	< 1	0.04	< 10	0.53	580	1
T 25704	201	238	1.58	0.6	30	260	< 0.5	< 2	0.79	< 0.5	13	27	34	3.60	10	< 1	0.10	20	0.56	600	5
T 25705	201	238	1.30	0.4	10	170	< 0.5	< 2	0.77	< 0.5	8	24	39	3.43	10	< 1	0.09	20	0.37	865	2
T 25706	201	238	1.04	0.2	< 5	120	< 0.5	< 2	0.37	1.0	19	19	72	6.05	10	< 1	0.10	20	0.29	3270	3
T 25707	201	238	0.40	< 0.2	5	450	< 0.5	< 2	12.10	0.5	15	7	53	3.75	< 10	< 1	0.05	< 10	7.51	3180	1
T 25708	201	238	1.43	1.2	< 5	360	< 0.5	< 2	1.04	1.5	17	21	65	7.81	20	< 1	0.10	20	0.46	4570	3
T 25709	201	238	1.39	0.4	15	120	0.5	< 2	0.15	< 0.5	15	22	35	5.00	10	< 1	0.19	20	0.32	1350	4
T 25710	201	238	1.83	0.2	5	160	< 0.5	< 2	0.17	< 0.5	10	23	19	3.72	10	< 1	0.15	20	0.36	990	2
T 25711	201	238	1.93	0.6	20	190	0.5	< 2	0.31	< 0.5	12	25	21	4.24	10	< 1	0.11	30	0.46	1045	1
T 25712	201	238	1.69	1.2	< 5	160	0.5	< 2	0.72	0.5	14	29	31	4.70	10	< 1	0.17	30	0.63	1405	< 1
T 25713	201	238	1.71	< 0.2	< 5	620	< 0.5	< 2	2.35	1.0	21	32	67	7.67	20	1	0.09	10	1.62	6220	< 1
T 25714	201	238	1.28	< 0.2	< 5	280	< 0.5	< 2	5.97	1.0	18	21	50	7.07	10	< 1	0.05	< 10	3.85	6820	< 1
T 25715	201	238	0.82	< 0.2	< 5	180	< 0.5	< 2	10.55	< 0.5	13	16	36	5.52	< 10	< 1	0.04	< 10	6.61	5460	< 1
T 25716	201	238	0.81	< 0.2	< 5	190	< 0.5	< 2	9.97	< 0.5	15	14	39	6.12	< 10	< 1	0.02	< 10	6.28	6260	< 1
T 25717	201	238	1.07	< 0.2	< 5	240	< 0.5	< 2	9.14	0.5	16	18	49	7.18	10	< 1	0.04	< 10	5.78	6940	< 1
T 25718	201	238	1.02	< 0.2	25	290	< 0.5	< 2	8.05	< 0.5	18	15	65	9.01	10	< 1	0.04	< 10	5.06	9740	< 1
T 25719	201	238	0.66	< 0.2	< 5	160	< 0.5	< 2	11.65	0.5	15	11	56	5.84	< 10	< 1	0.03	< 10	7.27	6110	< 1
T 25720	201	238	1.26	< 0.2	10	270	< 0.5	< 2	6.61	0.5	18	22	64	6.96	10	< 1	0.05	< 10	4.23	6730	< 1
T 25721	201	238	1.06	< 0.2	20	440	< 0.5	< 2	8.04	< 0.5	17	17	62	7.57	10	< 1	0.04	< 10	5.09	7800	< 1
T 25722	201	238	0.30	< 0.2	35	390	< 0.5	< 2	12.80	1.5	26	5	94	4.92	< 10	1	0.01	< 10	7.91	4740	1
T 25723	201	238	0.47	< 0.2	20	690	< 0.5	< 2	10.05	4.0	30	6	107	6.85	< 10	< 1	0.01	< 10	6.26	6620	2
T 25724	201	238	0.76	< 0.2	15	1140	< 0.5	< 2	7.44	1.5	27	13	75	7.24	10	< 1	0.03	< 10	4.63	6980	< 1
T 25725	201	238	0.32	< 0.2	10	270	< 0.5	< 2	14.25	1.0	18	5	49	4.07	< 10	< 1	0.01	< 10	8.86	3940	< 1
T 25726	201	238	0.60	< 0.2	25	580	< 0.5	< 2	9.94	0.5	20	8	105	6.97	10	< 1	0.03	< 10	6.09	6990	< 1
T 25727	201	238	1.20	< 0.2	15	760	< 0.5	< 2	4.70	1.0	26	19	95	8.57	20	< 1	0.07	< 10	2.68	7260	1
T 25728	201	238	1.31	1.2	10	640	< 0.5	< 2	4.42	1.0	17	21	35	9.08	20	< 1	0.06	< 10	2.43	6020	< 1
T 25729	201	238	0.40	< 0.2	10	870	< 0.5	< 2	13.95	0.5	17	6	59	4.58	< 10	1	0.03	< 10	8.64	3950	< 1
T 25730	201	238	0.40	< 0.2	45	290	< 0.5	< 2	13.65	< 0.5	27	5	57	5.37	< 10	< 1	0.01	< 10	8.42	4720	7
T 25731	201	238	0.25	< 0.2	< 5	110	< 0.5	< 2	>15.00	0.5	16	2	24	4.03	< 10	< 1	0.01	< 10	9.30	3460	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 25680	201	238	0.01	28	1280	134	< 5	4	19	0.05	< 10	< 10	71	< 10	346
T 25681	201	238	0.01	26	1800	162	< 5	5	20	0.04	< 10	< 10	67	< 10	356
T 25682	201	238	0.01	20	910	184	5	4	46	0.03	< 10	< 10	48	< 10	364
T 25683	201	238	0.01	24	1740	78	5	3	22	0.03	< 10	< 10	66	< 10	272
T 25684	201	238	0.01	25	1490	220	< 5	6	16	0.03	< 10	< 10	67	< 10	410
T 25685	201	238	0.01	32	1070	216	5	6	21	0.05	< 10	< 10	64	< 10	364
T 25686	201	238	0.01	23	1090	94	< 5	7	24	0.07	< 10	< 10	68	< 10	316
T 25687	201	238	0.01	27	1720	112	5	6	29	0.05	< 10	< 10	91	< 10	546
T 25688	201	238	0.01	24	1340	194	5	6	19	0.04	< 10	< 10	54	< 10	508
T 25689	201	238	0.01	29	1410	116	< 5	7	26	0.04	< 10	< 10	76	< 10	314
T 25690	201	238	0.01	22	1260	128	5	6	22	0.04	< 10	< 10	71	< 10	220
T 25703	201	238	0.01	16	2720	30	< 5	1	136	0.01	< 10	< 10	20	< 10	56
T 25704	201	238	0.01	39	2760	54	< 5	3	76	0.02	< 10	< 10	41	< 10	284
T 25705	201	238	0.01	20	1540	60	< 5	4	29	0.03	< 10	< 10	49	< 10	328
T 25706	201	238	0.01	37	1150	90	5	5	19	0.03	< 10	< 10	68	< 10	502
T 25707	201	238	0.01	24	470	150	10	2	27	0.01	< 10	< 10	15	10	310
T 25708	201	238	0.01	43	1880	222	5	5	19	0.03	< 10	< 10	42	< 10	558
T 25709	201	238	0.01	32	980	122	< 5	2	23	0.02	< 10	< 10	50	< 10	242
T 25710	201	238	0.01	18	560	130	< 5	3	12	0.03	< 10	< 10	50	< 10	200
T 25711	201	238	0.01	23	700	154	5	6	12	0.03	< 10	< 10	43	< 10	268
T 25712	201	238	0.01	30	1210	242	5	8	23	0.05	< 10	< 10	47	< 10	314
T 25713	201	238	0.01	37	890	146	5	5	18	0.06	< 10	< 10	54	< 10	344
T 25714	201	238	0.01	33	620	50	5	4	17	0.04	< 10	< 10	38	10	224
T 25715	201	238	0.01	23	410	30	5	2	19	0.03	< 10	< 10	25	10	158
T 25716	201	238	0.01	23	410	28	10	2	18	0.03	< 10	< 10	24	10	166
T 25717	201	238	0.01	31	500	32	5	3	19	0.04	< 10	< 10	32	10	196
T 25718	201	238	0.01	36	620	42	5	3	19	0.03	< 10	< 10	32	10	244
T 25719	201	238	0.01	26	350	24	5	2	19	0.02	< 10	< 10	22	10	172
T 25720	201	238	0.01	40	630	52	10	3	19	0.04	< 10	< 10	38	10	242
T 25721	201	238	0.01	32	660	84	10	3	18	0.03	< 10	< 10	36	10	248
T 25722	201	238	0.01	37	220	518	10	2	22	0.01	< 10	< 10	13	10	468
T 25723	201	238	0.01	58	410	690	10	2	22	0.01	< 10	< 10	19	10	758
T 25724	201	238	0.01	47	640	320	10	3	20	0.02	< 10	< 10	27	10	498
T 25725	201	238	0.01	25	190	198	5	1	17	0.01	< 10	< 10	12	10	314
T 25726	201	238	0.01	33	680	92	10	3	17	0.02	< 10	< 10	18	20	540
T 25727	201	238	0.01	41	1390	166	5	4	19	0.03	< 10	< 10	35	20	574
T 25728	201	238	0.01	26	1560	1630	10	5	24	0.03	< 10	< 10	37	20	466
T 25729	201	238	0.01	14	250	438	5	2	25	0.01	< 10	< 10	17	10	258
T 25730	201	238	0.02	43	260	194	5	2	17	0.01	< 10	< 10	14	20	392
T 25731	201	238	0.01	13	120	90	5	1	16	0.01	< 10	< 10	9	10	160

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 25732	201	238	0.51	< 0.2	< 5	360	< 0.5	< 2	12.40	1.0	19	5	146	4.90	< 10	< 1	0.04	< 10	7.42	4180	< 1
T 25733	201	238	1.50	1.4	20	580	< 0.5	< 2	1.79	3.5	32	21	113	11.05	20	< 1	0.07	20	0.95	9540	< 1
T 25734	201	238	0.61	< 0.2	5	220	< 0.5	< 2	12.55	1.0	19	9	56	6.31	10	< 1	0.03	< 10	7.46	6320	< 1
T 25735	201	238	0.32	< 0.2	< 5	90	< 0.5	< 2	12.70	0.5	13	4	18	7.90	10	< 1	0.01	< 10	7.38	9980	< 1
T 25736	201	238	0.82	< 0.2	< 5	240	< 0.5	< 2	11.25	0.5	14	12	32	5.43	< 10	< 1	0.04	< 10	6.87	5510	< 1
T 25737	201	238	0.39	< 0.2	5	560	< 0.5	< 2	10.90	0.5	18	5	134	7.56	10	< 1	0.03	< 10	6.44	7590	1
T 25738	201	238	0.24	< 0.2	25	480	< 0.5	< 2	13.65	< 0.5	20	4	117	5.41	< 10	< 1	0.03	< 10	8.09	4820	< 1
T 25739	201	238	0.23	< 0.2	5	420	< 0.5	< 2	13.35	0.5	20	3	110	6.32	< 10	< 1	0.02	< 10	7.92	6000	< 1
T 25740	201	238	0.64	< 0.2	5	1340	< 0.5	< 2	4.93	1.0	26	9	214	13.90	30	< 1	0.03	< 10	2.85	>10000	< 1
T 25741	201	238	0.62	< 0.2	< 5	620	< 0.5	< 2	10.15	1.5	23	9	111	7.20	10	< 1	0.05	< 10	6.04	6940	< 1
T 25742	201	238	0.46	< 0.2	20	440	< 0.5	< 2	13.60	< 0.5	19	6	88	5.52	< 10	< 1	0.03	< 10	8.13	5630	< 1
T 25743	201	238	0.41	< 0.2	15	440	< 0.5	< 2	13.60	< 0.5	19	5	85	5.36	< 10	< 1	0.03	< 10	8.11	5480	< 1
T 25744	201	238	1.37	< 0.2	< 5	690	< 0.5	< 2	6.68	1.0	21	21	80	6.58	10	< 1	0.05	< 10	3.95	6110	< 1
T 25745	201	238	1.29	0.4	35	160	< 0.5	< 2	3.84	0.5	14	23	38	5.34	10	< 1	0.08	< 10	2.39	3000	< 1
T 25746	201	238	0.42	< 0.2	25	230	< 0.5	< 2	12.05	< 0.5	17	8	55	3.59	< 10	< 1	0.05	< 10	7.09	2810	1
T 25747	201	238	1.22	0.2	15	200	< 0.5	< 2	0.45	< 0.5	17	29	72	5.37	10	< 1	0.13	30	0.40	1230	4
T 25748	201	238	1.41	0.6	50	150	< 0.5	< 2	0.27	< 0.5	26	26	174	6.19	10	< 1	0.09	30	0.49	825	2
T 25749	201	238	1.70	0.2	25	190	< 0.5	< 2	0.25	2.0	14	29	73	3.75	10	< 1	0.10	20	0.43	965	1
T 25750	201	238	1.14	0.8	10	170	< 0.5	< 2	0.46	< 0.5	20	21	52	5.02	10	< 1	0.10	20	0.39	1395	1
T 25763	201	238	0.75	< 0.2	20	130	< 0.5	< 2	4.85	< 0.5	24	15	34	6.15	10	< 1	0.06	< 10	2.83	4370	< 1
T 25764	201	238	0.80	< 0.2	25	120	< 0.5	< 2	6.32	< 0.5	21	15	27	4.73	10	< 1	0.10	< 10	3.75	2680	< 1
T 25765	201	238	0.82	< 0.2	15	160	< 0.5	< 2	5.67	< 0.5	21	16	34	4.72	10	< 1	0.06	< 10	3.33	3750	< 1
T 25766	201	238	0.65	< 0.2	25	100	< 0.5	< 2	12.70	< 0.5	21	15	27	3.02	< 10	< 1	0.08	< 10	7.75	2740	1
T 25767	201	238	1.52	1.4	20	170	< 0.5	< 2	2.48	< 0.5	25	29	54	4.59	10	< 1	0.16	< 10	1.09	3100	< 1
T 25768	201	238	0.34	< 0.2	35	50	< 0.5	< 2	14.00	< 0.5	22	11	24	2.75	< 10	< 1	0.06	< 10	8.38	1220	1
T 25769	201	238	0.79	< 0.2	20	100	< 0.5	< 2	4.76	< 0.5	34	18	38	4.85	10	< 1	0.07	< 10	2.96	4820	< 1
T 25770	201	238	0.80	< 0.2	5	100	< 0.5	< 2	4.67	0.5	31	15	33	4.62	10	< 1	0.07	< 10	2.82	3400	< 1
T 25771	201	238	0.36	< 0.2	10	100	< 0.5	< 2	11.55	< 0.5	20	5	453	2.36	< 10	< 1	0.05	< 10	5.48	1245	< 1
T 25772	201	238	1.05	< 0.2	15	150	< 0.5	< 2	5.56	< 0.5	18	20	27	3.35	< 10	< 1	0.09	< 10	3.53	1215	< 1
T 25773	201	238	0.74	< 0.2	30	100	< 0.5	< 2	12.30	< 0.5	14	16	18	2.27	< 10	< 1	0.07	< 10	7.65	1095	11
T 25774	201	238	1.25	0.4	< 5	120	< 0.5	< 2	1.09	0.5	20	27	25	3.78	10	3	0.09	20	0.52	1275	3
T 25775	201	238	0.93	< 0.2	45	110	< 0.5	< 2	8.41	< 0.5	25	20	27	3.74	< 10	< 1	0.08	< 10	5.14	1580	14
T 25826	201	238	1.00	< 0.2	5	80	< 0.5	< 2	10.20	< 0.5	10	18	12	1.57	< 10	< 1	0.04	< 10	6.53	795	2
T 25827	201	238	1.21	< 0.2	10	140	< 0.5	< 2	8.44	< 0.5	20	25	19	2.86	< 10	< 1	0.10	< 10	5.32	615	11
T 25828	201	238	1.60	< 0.2	5	160	< 0.5	< 2	5.66	0.5	16	30	34	3.38	< 10	2	0.07	< 10	3.64	1810	3
T 25829	201	238	1.52	< 0.2	10	130	< 0.5	< 2	4.97	< 0.5	13	25	16	2.90	< 10	2	0.08	< 10	3.18	915	1
T 25830	201	238	1.26	< 0.2	50	110	< 0.5	< 2	9.70	< 0.5	19	27	23	3.24	< 10	2	0.05	< 10	6.11	2450	2
T 25831	201	238	1.88	< 0.2	35	190	< 0.5	< 2	5.77	< 0.5	19	34	23	3.50	10	< 1	0.10	< 10	3.64	2160	2
T 25832	201	238	2.41	0.2	< 5	280	< 0.5	< 2	1.24	1.0	25	41	29	5.39	20	< 1	0.12	20	0.70	4760	< 1
T 25833	201	238	1.64	< 0.2	10	150	0.5	< 2	5.08	< 0.5	20	30	23	3.79	10	< 1	0.10	< 10	3.18	2930	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 25732	201	238	0.01	23	610	128	10	2	27	0.01	< 10	< 10	19	10	496
T 25733	201	238	0.01	49	1340	258	< 5	4	17	0.03	< 10	< 10	45	20	1315
T 25734	201	238	0.02	21	520	96	5	2	21	0.02	< 10	< 10	21	30	382
T 25735	201	238	0.02	6	640	14	5	1	22	< 0.01	< 10	< 10	15	40	242
T 25736	201	238	0.02	13	410	24	5	2	19	0.03	< 10	< 10	26	20	164
T 25737	201	238	0.01	24	530	110	10	3	25	0.01	< 10	< 10	18	30	306
T 25738	201	238	0.01	20	320	94	5	2	28	< 0.01	< 10	< 10	13	20	260
T 25739	201	238	0.01	20	350	80	10	3	27	< 0.01	< 10	< 10	15	30	226
T 25740	201	238	0.01	41	920	110	10	4	13	0.01	< 10	< 10	31	50	458
T 25741	201	238	0.01	31	680	146	5	3	19	0.02	< 10	< 10	24	30	356
T 25742	201	238	0.02	21	350	118	5	3	23	0.01	< 10	< 10	19	30	278
T 25743	201	238	0.01	20	330	106	5	3	23	0.01	< 10	< 10	17	20	274
T 25744	201	238	0.01	28	950	126	5	4	20	0.04	< 10	< 10	42	30	346
T 25745	201	238	0.01	26	720	572	< 5	6	18	0.04	< 10	< 10	39	20	664
T 25746	201	238	0.01	29	430	80	5	3	33	0.02	< 10	< 10	16	20	176
T 25747	201	238	0.01	50	1450	60	< 5	9	18	0.01	< 10	< 10	45	20	156
T 25748	201	238	0.01	74	960	128	< 5	7	22	0.04	< 10	< 10	41	20	184
T 25749	201	238	0.01	30	980	84	< 5	2	21	0.05	< 10	< 10	57	10	1120
T 25750	201	238	0.01	43	960	86	5	6	27	0.02	< 10	< 10	35	20	280
T 25763	201	238	0.01	27	1000	152	< 5	12	61	0.01	< 10	< 10	37	30	276
T 25764	201	238	0.01	20	1070	204	5	7	73	0.01	< 10	< 10	44	10	298
T 25765	201	238	0.01	24	1260	98	5	6	52	0.01	< 10	< 10	67	10	244
T 25766	201	238	0.02	18	1240	72	5	4	76	0.01	< 10	< 10	105	10	234
T 25767	201	238	0.01	26	1700	272	5	6	51	0.02	< 10	< 10	136	< 10	318
T 25768	201	238	0.01	21	1410	224	10	4	84	< 0.01	< 10	< 10	49	10	184
T 25769	201	238	0.01	26	1210	76	5	8	56	< 0.01	< 10	< 10	57	10	318
T 25770	201	238	0.01	22	1380	78	< 5	7	43	0.01	< 10	< 10	82	10	266
T 25771	201	238	0.01	13	490	44	5	5	126	< 0.01	< 10	< 10	11	10	128
T 25772	201	238	0.01	18	920	96	< 5	7	48	0.03	< 10	< 10	49	10	228
T 25773	201	238	0.02	20	810	46	5	2	40	0.02	< 10	< 10	46	< 10	136
T 25774	201	238	0.01	30	1150	58	5	7	72	0.03	< 10	< 10	50	< 10	380
T 25775	201	238	0.01	36	1120	246	5	4	41	0.02	< 10	< 10	47	10	376
T 25826	201	238	0.01	15	650	22	5	2	27	0.03	< 10	< 10	31	< 10	84
T 25827	201	238	0.01	34	1460	46	5	4	46	0.03	< 10	< 10	43	10	84
T 25828	201	238	0.01	24	1120	58	10	3	26	0.04	< 10	< 10	87	< 10	212
T 25829	201	238	0.01	20	1350	38	5	3	26	0.04	< 10	< 10	57	10	136
T 25830	201	238	0.01	26	1250	82	10	3	29	0.02	< 10	< 10	131	10	316
T 25831	201	238	0.02	28	1610	54	5	4	32	0.05	< 10	< 10	103	10	250
T 25832	201	238	0.01	34	2490	88	5	5	25	0.05	< 10	< 10	155	< 10	372
T 25833	201	238	0.01	25	1460	86	10	5	34	0.04	< 10	< 10	101	10	282

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 25834	201	238	1.63	< 0.2	5	140	< 0.5	< 2	5.37	0.5	15	30	20	3.24	10	< 1	0.10	< 10	3.47	1920	< 1
T 25835	201	238	1.68	< 0.2	20	160	0.5	< 2	3.50	< 0.5	18	32	25	4.33	10	< 1	0.11	< 10	2.31	2900	< 1
T 25836	201	238	1.82	1.2	15	190	< 0.5	< 2	1.17	1.0	15	40	26	4.81	10	< 1	0.08	10	0.72	2380	< 1
T 25837	201	238	1.52	2.8	5	180	< 0.5	< 2	0.47	2.0	13	25	24	7.32	10	< 1	0.08	10	0.42	3540	< 1
T 25851	201	238	1.11	0.4	5	100	< 0.5	< 2	0.38	< 0.5	14	22	37	4.47	10	< 1	0.15	30	0.52	1895	< 1
T 25852	201	238	1.30	0.4	30	120	< 0.5	< 2	0.72	< 0.5	13	24	43	5.04	10	< 1	0.24	30	0.68	2110	1
T 25853	201	238	1.49	0.4	30	140	0.5	< 2	0.66	< 0.5	13	25	37	5.34	10	< 1	0.14	20	0.56	2190	1
T 25854	201	238	1.03	0.6	10	100	< 0.5	< 2	1.69	< 0.5	73	21	154	4.55	10	< 1	0.16	20	1.01	2360	< 1
T 25855	201	238	1.32	0.8	< 5	160	< 0.5	< 2	0.87	< 0.5	83	20	155	4.65	10	< 1	0.19	30	0.57	2490	< 1
T 25856	201	238	1.38	0.8	25	1230	0.5	< 2	0.76	< 0.5	70	22	166	4.14	10	< 1	0.29	30	0.87	2100	< 1
T 25857	201	238	2.18	0.4	30	130	< 0.5	< 2	0.77	< 0.5	36	25	90	8.08	20	< 1	0.24	30	1.71	3730	< 1
T 25858	201	238	1.47	0.6	30	90	< 0.5	< 2	0.71	< 0.5	31	19	70	9.86	20	< 1	0.27	30	0.74	4030	< 1
T 25859	201	238	1.33	0.6	30	110	< 0.5	< 2	0.25	< 0.5	16	20	34	4.04	10	< 1	0.24	20	0.35	1170	2
T 25860	201	238	0.52	< 0.2	35	70	< 0.5	< 2	1.68	< 0.5	10	8	27	6.99	10	< 1	0.07	10	0.65	4980	< 1
T 25861	201	238	0.52	< 0.2	55	50	< 0.5	< 2	3.78	< 0.5	10	7	58	2.73	< 10	< 1	0.09	< 10	2.07	1950	< 1
T 25862	201	238	1.31	1.6	45	130	< 0.5	< 2	2.05	8.5	32	22	49	4.84	10	< 1	0.10	10	1.31	3740	< 1
T 25863	201	238	0.45	< 0.2	< 5	50	< 0.5	< 2	10.15	3.5	11	9	33	2.01	< 10	< 1	0.06	< 10	6.33	1540	< 1
T 25864	201	238	0.32	< 0.2	25	50	< 0.5	< 2	5.99	< 0.5	12	9	30	4.17	< 10	< 1	0.07	< 10	3.27	3660	< 1
T 25865	201	238	0.92	0.8	15	90	< 0.5	< 2	0.54	< 0.5	10	16	52	5.01	10	< 1	0.14	30	0.43	2540	< 1
T 25866	201	238	1.83	< 0.2	20	110	< 0.5	< 2	2.70	< 0.5	19	25	47	4.78	10	< 1	0.17	< 10	3.26	3730	< 1
T 25867	201	238	3.64	< 0.2	< 5	140	< 0.5	< 2	0.65	< 0.5	19	39	58	6.38	20	< 1	0.07	30	4.79	4510	< 1
T 25868	201	238	1.12	0.2	35	60	< 0.5	< 2	1.10	< 0.5	12	15	94	6.00	10	< 1	0.18	30	0.74	1610	< 1
T 25869	201	238	0.84	< 0.2	< 5	110	< 0.5	< 2	2.12	< 0.5	14	16	96	5.10	10	< 1	0.19	20	1.34	3640	< 1
T 25870	201	238	0.79	0.4	15	110	< 0.5	< 2	2.33	< 0.5	14	14	91	5.08	10	< 1	0.17	20	1.43	3650	< 1
T 25871	201	238	2.14	0.2	15	100	< 0.5	< 2	0.73	0.5	17	32	43	5.28	10	< 1	0.24	20	2.10	2730	< 1
T 25872	201	238	1.12	0.2	40	150	< 0.5	< 2	1.12	< 0.5	15	18	34	6.20	10	< 1	0.17	20	0.64	5020	< 1
T 25873	201	238	2.63	0.4	40	110	< 0.5	< 2	1.05	< 0.5	26	40	67	6.01	20	< 1	0.19	20	2.39	2190	< 1
T 25874	201	238	4.14	< 0.2	< 5	90	< 0.5	< 2	0.84	0.5	35	59	30	7.33	30	< 1	0.18	20	4.58	1590	< 1
T 25875	201	238	3.38	< 0.2	10	70	< 0.5	< 2	0.86	< 0.5	15	35	29	5.03	10	< 1	0.23	20	4.61	1830	< 1
T 25876	201	238	0.96	0.2	30	110	< 0.5	< 2	1.66	< 0.5	14	17	30	3.34	10	< 1	0.23	20	1.15	1845	< 1
T 25877	201	238	0.71	0.8	< 5	70	< 0.5	< 2	0.98	0.5	14	16	49	4.85	10	< 1	0.14	30	0.58	1380	< 1
T 25878	201	238	0.70	0.2	35	90	< 0.5	< 2	1.32	< 0.5	14	12	46	6.95	10	< 1	0.11	20	0.61	3760	< 1
T 25879	201	238	0.65	0.6	15	70	< 0.5	< 2	1.00	< 0.5	13	11	36	4.48	10	< 1	0.11	30	0.49	2310	< 1
T 25880	201	238	0.59	< 0.2	30	80	< 0.5	< 2	1.33	< 0.5	19	11	62	6.96	10	< 1	0.08	20	0.69	4550	< 1
T 25903	201	238	1.71	0.6	< 5	250	< 0.5	< 2	0.59	0.5	13	31	27	3.61	10	< 1	0.07	20	0.62	735	< 1
T 25904	201	238	2.06	0.4	15	200	< 0.5	< 2	1.50	0.5	15	31	20	4.59	10	< 1	0.07	20	0.98	2150	2
T 25905	201	238	1.40	0.2	< 5	310	< 0.5	< 2	1.55	3.5	15	26	24	5.20	10	< 1	0.10	10	0.62	3590	2
T 25906	201	238	1.05	0.4	20	240	< 0.5	< 2	0.57	< 0.5	14	18	28	5.80	10	< 1	0.14	30	0.29	2560	1
T 25907	201	238	1.10	< 0.2	50	380	< 0.5	< 2	1.27	< 0.5	17	14	24	9.35	20	< 1	0.06	10	0.41	8460	2
T 25908	201	238	2.41	0.2	35	200	< 0.5	< 2	0.28	< 0.5	9	40	17	3.79	10	< 1	0.13	20	0.63	630	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 25834	201	238	0.02	23	1260	44	5	5	37	0.05	< 10	< 10	87	< 10	232
T 25835	201	238	0.01	27	1230	64	< 5	5	33	0.05	< 10	< 10	105	< 10	268
T 25836	201	238	0.01	28	1360	360	5	6	25	0.05	< 10	< 10	104	< 10	448
T 25837	201	238	0.01	27	920	1570	5	7	14	0.03	< 10	< 10	64	< 10	1240
T 25851	201	238	0.01	21	610	26	< 5	5	14	0.06	< 10	< 10	33	< 10	80
T 25852	201	238	0.01	25	1100	70	< 5	6	15	0.04	< 10	< 10	32	< 10	132
T 25853	201	238	0.01	23	1190	54	5	6	14	0.04	< 10	< 10	39	< 10	122
T 25854	201	238	0.01	76	1210	134	10	8	16	0.04	< 10	< 10	32	< 10	256
T 25855	201	238	0.01	92	1380	162	5	8	17	0.04	< 10	< 10	40	< 10	176
T 25856	201	238	0.01	58	970	102	5	6	19	0.06	< 10	< 10	37	< 10	316
T 25857	201	238	0.01	38	1180	86	5	13	20	0.05	< 10	< 10	78	< 10	570
T 25858	201	238	0.01	41	1550	104	10	12	21	0.02	< 10	< 10	54	< 10	204
T 25859	201	238	0.01	17	2110	26	< 5	1	11	0.01	< 10	< 10	42	< 10	90
T 25860	201	238	0.01	15	1220	50	5	4	21	0.01	< 10	< 10	12	< 10	134
T 25861	201	238	0.01	11	760	16	5	4	29	0.01	< 10	< 10	10	< 10	38
T 25862	201	238	0.01	34	850	1325	10	5	20	0.04	< 10	< 10	40	10	7180
T 25863	201	238	0.02	10	420	266	10	3	25	0.02	< 10	< 10	15	< 10	2810
T 25864	201	238	0.01	14	630	54	5	5	51	0.01	< 10	< 10	12	< 10	280
T 25865	201	238	0.01	20	740	46	5	7	14	0.03	< 10	< 10	29	< 10	158
T 25866	201	238	0.01	28	730	46	5	7	26	0.04	< 10	< 10	40	10	168
T 25867	201	238	0.01	30	910	20	< 5	15	11	0.03	< 10	< 10	52	< 10	326
T 25868	201	238	0.01	20	1170	12	< 5	7	18	0.02	< 10	< 10	29	< 10	130
T 25869	201	238	0.01	23	840	64	5	7	21	0.04	< 10	< 10	26	< 10	144
T 25870	201	238	0.01	24	780	50	5	6	20	0.03	< 10	< 10	25	10	142
T 25871	201	238	0.01	27	900	64	< 5	8	13	0.06	< 10	< 10	55	< 10	592
T 25872	201	238	0.01	26	1370	54	5	6	20	0.02	< 10	< 10	29	< 10	186
T 25873	201	238	0.01	29	950	42	5	13	13	0.20	< 10	< 10	109	10	338
T 25874	201	238	0.01	35	700	140	5	15	13	0.47	< 10	< 10	185	10	1255
T 25875	201	238	0.01	27	860	20	5	10	10	0.02	< 10	< 10	48	< 10	348
T 25876	201	238	0.01	20	820	36	5	5	24	0.05	< 10	< 10	31	< 10	438
T 25877	201	238	0.01	21	870	86	5	6	17	0.02	< 10	< 10	23	< 10	246
T 25878	201	238	0.01	24	1180	40	5	6	19	0.01	< 10	< 10	18	< 10	324
T 25879	201	238	0.01	16	1050	30	< 5	5	15	0.01	< 10	< 10	17	< 10	210
T 25880	201	238	0.01	22	910	28	5	6	22	0.01	< 10	< 10	17	10	142
T 25903	201	238	0.01	25	870	56	< 5	6	19	0.04	< 10	< 10	51	< 10	168
T 25904	201	238	0.01	26	1250	116	< 5	6	19	0.03	< 10	< 10	77	< 10	286
T 25905	201	238	0.01	23	1960	146	5	4	26	0.03	< 10	< 10	63	10	780
T 25906	201	238	0.01	22	1110	50	5	8	18	0.01	< 10	< 10	33	10	212
T 25907	201	238	0.01	21	2610	50	5	8	25	0.01	< 10	< 10	35	10	256
T 25908	201	238	0.01	25	850	38	< 5	4	21	0.07	< 10	< 10	75	< 10	208

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 25909	201	238	2.28	0.2	5	210	< 0.5	< 2	0.40	< 0.5	5	36	12	3.17	10	< 1	0.11	20	0.58	295	< 1
T 25910	201	238	2.01	0.4	< 5	190	< 0.5	< 2	0.25	0.5	14	33	18	4.75	10	< 1	0.09	30	0.52	1885	1
T 25911	201	238	2.12	0.4	45	250	< 0.5	< 2	0.83	< 0.5	16	32	23	5.09	10	1	0.10	20	0.63	2930	< 1
T 25912	201	238	1.59	1.0	15	140	< 0.5	< 2	0.86	< 0.5	13	26	20	5.04	10	1	0.10	20	0.46	1390	< 1
T 25913	201	238	2.54	0.4	20	220	< 0.5	< 2	0.49	< 0.5	8	36	11	3.61	10	< 1	0.09	20	0.57	570	< 1
T 25914	201	238	1.74	0.2	< 5	200	< 0.5	< 2	2.38	0.5	13	29	19	4.09	10	< 1	0.07	< 10	1.60	1775	< 1
T 25915	201	238	1.71	0.2	40	190	< 0.5	< 2	1.67	< 0.5	12	31	24	4.50	10	< 1	0.09	10	1.14	1945	< 1
T 25916	201	238	1.92	0.6	5	260	< 0.5	< 2	1.02	0.5	12	32	26	4.87	10	< 1	0.09	20	0.69	1890	< 1
T 25917	201	238	2.33	0.4	25	240	< 0.5	< 2	0.57	< 0.5	11	37	17	4.18	10	1	0.09	20	0.69	1290	< 1
T 25918	201	238	1.15	0.8	10	160	< 0.5	< 2	6.05	0.5	17	20	35	4.67	< 10	< 1	0.06	< 10	3.72	3140	< 1
T 25919	201	238	1.38	0.8	35	560	< 0.5	4	3.12	< 0.5	16	23	46	5.96	10	< 1	0.08	< 10	1.99	3400	< 1
T 25920	201	238	1.55	1.0	25	180	< 0.5	< 2	1.10	< 0.5	16	27	28	5.56	10	1	0.09	10	0.66	2360	1
T 25921	201	238	2.35	0.2	25	200	< 0.5	< 2	0.64	< 0.5	8	38	14	3.73	10	< 1	0.10	20	0.66	860	< 1
T 25922	201	238	1.77	< 0.2	10	180	< 0.5	2	3.31	0.5	14	31	21	4.30	10	< 1	0.10	< 10	2.27	2560	< 1
T 25923	201	238	2.07	0.4	< 5	240	< 0.5	< 2	0.59	1.0	14	33	19	4.44	10	< 1	0.10	20	0.58	2150	1
T 25924	201	238	2.12	0.4	30	190	< 0.5	< 2	0.43	< 0.5	9	35	16	4.19	10	< 1	0.12	20	0.60	1095	1
T 25925	201	238	1.66	< 0.2	20	180	< 0.5	< 2	2.56	< 0.5	13	30	23	3.87	10	< 1	0.10	< 10	1.72	1860	< 1
T 25926	201	238	1.85	0.4	30	150	< 0.5	< 2	0.89	< 0.5	11	31	22	4.21	10	< 1	0.08	20	0.60	1365	< 1
T 25927	201	238	1.89	0.2	10	150	< 0.5	< 2	0.64	< 0.5	10	33	22	4.13	10	< 1	0.08	20	0.54	1310	< 1
T 25928	201	238	0.75	< 0.2	20	80	< 0.5	< 2	8.71	< 0.5	13	14	30	2.69	< 10	5	0.06	< 10	5.54	1115	1
T 25929	201	238	1.17	< 0.2	< 5	140	< 0.5	< 2	2.33	0.5	16	24	29	4.03	10	< 1	0.08	< 10	1.47	1525	< 1
T 25930	201	238	1.36	< 0.2	25	160	< 0.5	< 2	3.35	< 0.5	13	27	28	3.73	10	< 1	0.09	< 10	2.20	1425	< 1
T 25931	201	238	1.02	< 0.2	15	120	< 0.5	< 2	6.10	< 0.5	11	21	20	2.88	< 10	< 1	0.07	< 10	3.93	1265	1
T 25932	201	238	1.74	0.4	< 5	190	< 0.5	2	0.74	< 0.5	10	29	20	3.91	10	< 1	0.07	20	0.74	620	< 1
T 25933	201	238	1.78	0.2	10	180	< 0.5	< 2	0.87	< 0.5	13	29	21	3.92	10	< 1	0.08	20	0.74	1340	< 1
T 25934	201	238	2.26	1.6	5	180	< 0.5	< 2	0.75	0.5	8	36	16	6.97	20	2	0.08	20	0.72	1535	< 1
T 25935	201	238	1.88	0.2	10	190	< 0.5	< 2	0.86	< 0.5	12	28	16	3.69	10	< 1	0.10	10	0.62	1020	2
T 25936	201	238	1.90	1.4	30	170	< 0.5	< 2	0.99	0.5	11	31	20	4.01	10	< 1	0.09	20	0.64	1210	< 1
T 25937	201	238	1.83	0.8	10	200	< 0.5	4	1.03	1.5	11	31	16	4.10	10	< 1	0.10	10	0.68	1910	< 1
T 25938	201	238	1.69	0.6	< 5	240	< 0.5	2	4.35	2.0	14	27	20	4.51	10	< 1	0.10	< 10	2.87	2950	< 1
T 25939	201	238	1.72	0.6	20	200	< 0.5	< 2	1.01	0.5	11	30	24	4.53	10	< 1	0.12	20	0.68	2010	< 1
T 25940	201	238	2.01	0.4	< 5	280	< 0.5	< 2	1.06	1.0	13	33	20	4.54	10	< 1	0.12	20	0.67	2440	1
T 25941	201	238	2.91	0.4	30	280	< 0.5	2	0.49	< 0.5	9	42	11	4.03	20	< 1	0.12	20	0.64	1045	< 1
T 25942	201	238	1.89	1.0	35	230	< 0.5	< 2	0.67	< 0.5	13	32	19	5.23	10	< 1	0.12	30	0.55	1885	< 1
T 25943	201	238	1.47	0.4	25	300	< 0.5	< 2	1.49	< 0.5	11	29	21	3.74	10	< 1	0.10	10	0.77	1125	< 1
T 25944	201	238	1.91	0.4	40	180	< 0.5	< 2	0.40	< 0.5	7	30	14	4.52	10	< 1	0.08	20	0.43	830	< 1
T 25945	201	238	1.14	0.2	< 5	170	< 0.5	< 2	1.54	0.5	14	22	27	4.19	10	< 1	0.07	20	0.94	1445	< 1
T 25946	201	238	2.54	0.4	15	180	< 0.5	< 2	0.69	< 0.5	12	41	17	4.46	10	< 1	0.11	20	0.65	1430	< 1
T 25947	201	238	2.27	0.6	10	210	< 0.5	< 2	0.49	< 0.5	6	35	17	3.77	10	< 1	0.11	30	0.65	530	< 1
T 25948	201	238	2.19	0.4	55	400	< 0.5	< 2	0.35	< 0.5	9	36	31	4.33	10	< 1	0.09	20	0.49	1045	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 27-AUG-89
Invoice # : I-8923491
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923491

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 25909	201 238	0.01	19	1430	32	< 5	3	20	0.05	< 10	< 10	68	< 10	156
T 25910	201 238	0.01	24	820	98	< 5	5	17	0.05	< 10	< 10	68	< 10	240
T 25911	201 238	0.01	29	1280	92	5	6	19	0.04	< 10	< 10	66	< 10	234
T 25912	201 238	0.01	19	1310	98	5	8	19	0.03	< 10	< 10	49	< 10	252
T 25913	201 238	0.01	19	620	28	< 5	5	21	0.07	< 10	< 10	73	< 10	136
T 25914	201 238	0.01	21	940	96	5	6	24	0.04	< 10	< 10	57	10	198
T 25915	201 238	0.01	21	1110	116	5	5	19	0.04	< 10	< 10	63	< 10	280
T 25916	201 238	0.01	21	1310	154	5	5	18	0.03	< 10	< 10	70	< 10	298
T 25917	201 238	0.01	25	830	80	< 5	6	19	0.06	< 10	< 10	72	< 10	218
T 25918	201 238	0.01	20	1300	284	10	4	36	0.01	< 10	< 10	54	10	288
T 25919	201 238	0.01	24	1270	380	5	5	21	0.02	< 10	< 10	59	10	448
T 25920	201 238	0.01	25	1270	304	5	5	18	0.03	< 10	< 10	73	10	412
T 25921	201 238	0.01	20	1030	66	< 5	5	19	0.06	< 10	< 10	74	< 10	210
T 25922	201 238	0.01	24	1210	84	5	6	24	0.04	< 10	< 10	63	< 10	272
T 25923	201 238	0.01	22	1620	150	5	5	21	0.05	< 10	< 10	70	< 10	498
T 25924	201 238	0.01	23	980	178	< 5	5	21	0.06	< 10	< 10	64	< 10	374
T 25925	201 238	0.02	22	1160	164	< 5	5	27	0.05	< 10	< 10	66	< 10	312
T 25926	201 238	0.01	21	1350	178	< 5	6	21	0.05	< 10	< 10	64	< 10	240
T 25927	201 238	0.01	21	1370	162	5	6	22	0.04	< 10	< 10	72	< 10	246
T 25928	201 238	0.01	17	800	100	5	5	49	0.02	< 10	< 10	36	< 10	184
T 25929	201 238	0.01	22	990	124	5	7	27	0.03	< 10	< 10	51	< 10	244
T 25930	201 238	0.01	22	990	54	5	7	38	0.05	< 10	< 10	58	10	146
T 25931	201 238	0.01	17	880	52	5	5	44	0.04	< 10	< 10	54	< 10	146
T 25932	201 238	0.01	25	710	122	< 5	7	24	0.05	< 10	< 10	49	< 10	256
T 25933	201 238	0.01	19	1200	184	< 5	5	22	0.04	< 10	< 10	49	< 10	322
T 25934	201 238	0.01	26	860	666	< 5	8	19	0.06	< 10	< 10	72	10	774
T 25935	201 238	0.01	14	1440	122	< 5	4	27	0.04	< 10	< 10	54	< 10	264
T 25936	201 238	0.01	19	1190	628	< 5	5	27	0.05	< 10	< 10	58	< 10	952
T 25937	201 238	0.01	18	1110	706	5	5	21	0.05	< 10	< 10	56	< 10	848
T 25938	201 238	0.01	21	1060	554	5	6	31	0.05	< 10	< 10	57	10	1025
T 25939	201 238	0.01	25	1090	288	5	5	23	0.05	< 10	< 10	57	< 10	690
T 25940	201 238	0.01	21	1370	146	< 5	6	23	0.05	< 10	< 10	61	< 10	404
T 25941	201 238	0.01	20	620	52	5	5	26	0.10	< 10	< 10	91	< 10	146
T 25942	201 238	0.01	21	1070	184	< 5	7	18	0.05	< 10	< 10	60	< 10	360
T 25943	201 238	0.02	19	1150	64	5	5	24	0.04	< 10	< 10	43	< 10	268
T 25944	201 238	0.01	15	830	24	< 5	7	14	0.04	< 10	< 10	51	< 10	176
T 25945	201 238	0.01	22	890	34	5	7	23	0.03	< 10	< 10	34	< 10	186
T 25946	201 238	0.02	23	1110	70	< 5	6	20	0.06	< 10	< 10	78	< 10	226
T 25947	201 238	0.01	22	990	50	< 5	6	21	0.06	< 10	< 10	60	< 10	170
T 25948	201 238	0.01	32	690	86	5	5	17	0.06	< 10	< 10	60	< 10	170

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page N :1-A
Tot. F 6
Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 25949	201	238	0.95	1.0	60	1080	< 0.5	< 2	3.52	1.0	44	16	145	11.05	20	< 1	0.03	< 10	2.28	9390	< 1
T 25950	201	238	2.40	0.4	15	320	< 0.5	< 2	0.33	< 0.5	9	37	25	5.47	10	< 1	0.06	20	0.53	1620	< 1
T 26001	201	238	2.50	< 0.2	5	190	< 0.5	< 2	0.38	< 0.5	6	40	12	3.87	10	< 1	0.08	20	0.56	540	< 1
T 26002	201	238	1.98	0.2	10	180	< 0.5	< 2	0.38	< 0.5	3	33	12	5.88	10	< 1	0.06	20	0.51	1310	< 1
T 26003	201	238	2.01	0.4	5	150	< 0.5	< 2	0.20	< 0.5	5	31	11	3.03	10	< 1	0.09	20	0.48	370	< 1
T 26004	201	238	1.80	6.0	35	140	< 0.5	< 2	0.91	2.5	17	33	39	4.56	10	< 1	0.13	30	0.89	2040	< 1
T 26005	201	238	1.55	4.2	30	140	< 0.5	< 2	0.92	1.0	13	27	37	4.83	10	< 1	0.11	30	0.88	2160	< 1
T 26006	201	238	2.13	0.4	40	170	< 0.5	< 2	0.27	< 0.5	11	32	19	4.36	10	< 1	0.10	20	0.53	1280	< 1
T 26007	201	238	2.53	0.4	20	230	< 0.5	< 2	0.41	< 0.5	7	39	16	4.21	10	< 1	0.10	30	0.60	770	< 1
T 26008	201	238	2.23	0.2	10	210	< 0.5	< 2	0.29	< 0.5	6	37	13	3.50	10	< 1	0.10	20	0.54	610	< 1
T 26009	201	238	2.37	0.6	25	220	< 0.5	< 2	0.35	< 0.5	7	40	14	4.76	10	< 1	0.09	20	0.62	1050	< 1
T 26010	201	238	2.10	0.4	25	170	< 0.5	< 2	0.39	< 0.5	5	37	12	4.00	10	< 1	0.12	20	0.59	770	< 1
T 26011	201	238	2.20	0.4	< 5	170	< 0.5	< 2	0.30	< 0.5	6	40	13	3.84	10	< 1	0.07	20	0.58	510	< 1
T 26012	201	238	2.39	0.8	20	440	< 0.5	< 2	0.42	< 0.5	9	36	16	9.69	20	< 1	0.05	30	0.44	8570	< 1
T 26013	201	238	2.22	0.2	30	200	< 0.5	< 2	0.22	< 0.5	6	34	12	3.37	10	< 1	0.07	20	0.54	665	< 1
T 26014	201	238	1.74	0.2	< 5	130	< 0.5	< 2	0.16	< 0.5	5	30	11	3.17	10	< 1	0.04	10	0.41	450	< 1
T 26015	201	238	1.00	3.0	30	90	< 0.5	< 2	0.22	1.5	13	16	26	4.88	10	3	0.08	30	0.34	3020	< 1
T 26016	201	238	0.48	0.8	25	1020	< 0.5	< 2	11.05	< 0.5	17	12	33	3.83	< 10	< 1	0.04	< 10	6.77	2920	< 1
T 26017	201	238	0.67	1.6	195	1460	< 0.5	< 2	1.72	0.5	36	13	142	7.49	10	< 1	0.06	< 10	1.09	2560	2
T 26018	201	238	1.31	0.8	10	210	< 0.5	< 2	1.19	0.5	16	24	39	5.13	10	< 1	0.15	20	0.71	2820	< 1
T 26019	201	238	2.19	0.2	20	180	< 0.5	< 2	0.31	< 0.5	9	37	13	3.28	10	< 1	0.08	20	0.57	590	< 1
T 26020	201	238	2.58	0.6	15	240	< 0.5	< 2	0.29	< 0.5	5	45	13	3.56	10	1	0.13	20	0.61	415	< 1
T 26021	201	238	1.90	0.4	35	200	< 0.5	< 2	0.28	< 0.5	9	34	14	3.91	10	< 1	0.12	20	0.49	1160	< 1
T 26022	201	238	2.62	0.4	5	300	< 0.5	< 2	0.68	0.5	12	44	14	3.97	10	< 1	0.11	20	0.73	1235	< 1
T 26023	201	238	2.51	0.2	20	250	< 0.5	< 2	0.42	< 0.5	10	43	15	3.59	10	< 1	0.12	20	0.65	695	< 1
T 26024	201	238	2.21	0.4	15	220	< 0.5	< 2	0.39	< 0.5	6	37	12	3.25	10	< 1	0.12	20	0.61	365	< 1
T 26025	201	238	2.16	0.4	10	200	< 0.5	< 2	0.29	< 0.5	9	38	16	4.06	10	< 1	0.11	20	0.58	745	< 1
T 26026	201	238	2.03	0.8	5	210	< 0.5	< 2	0.61	< 0.5	11	38	21	4.56	10	< 1	0.10	20	0.62	1085	< 1
T 26027	201	238	1.79	1.8	< 5	170	< 0.5	< 2	0.95	2.0	13	32	21	5.22	10	< 1	0.09	20	0.59	2330	< 1
T 26028	201	238	1.97	0.8	5	200	< 0.5	< 2	0.82	1.0	14	36	24	4.33	10	< 1	0.10	20	0.75	1510	< 1
T 26029	201	238	1.49	1.6	< 5	190	< 0.5	< 2	1.03	3.0	14	24	20	5.50	10	< 1	0.08	20	0.54	3590	< 1
T 26030	201	238	2.10	0.8	20	180	< 0.5	< 2	0.64	0.5	12	32	21	4.34	10	< 1	0.09	20	0.61	1470	< 1
T 26031	201	238	1.96	0.6	< 5	210	< 0.5	< 2	0.84	2.0	16	29	24	4.08	10	< 1	0.10	10	0.51	3280	< 1
T 26032	201	238	1.88	0.6	< 5	180	< 0.5	< 2	0.46	1.5	13	32	20	4.40	10	< 1	0.09	20	0.55	1500	< 1
T 26033	201	238	0.29	< 0.2	10	70	< 0.5	< 2	14.25	< 0.5	8	5	14	3.91	< 10	< 1	0.01	< 10	8.57	4550	< 1
T 26034	201	238	0.15	< 0.2	5	110	< 0.5	< 2	>15.00	< 0.5	12	5	24	3.29	< 10	6	0.01	< 10	9.42	3660	< 1
T 26035	201	238	0.31	< 0.2	15	70	< 0.5	< 2	>15.00	< 0.5	10	4	13	3.50	< 10	< 1	0.02	< 10	9.43	3910	< 1
T 26036	201	238	0.16	< 0.2	< 5	70	< 0.5	< 2	>15.00	1.0	11	3	25	3.10	< 10	< 1	0.01	< 10	10.00	3370	< 1
T 26037	201	238	0.19	< 0.2	5	120	< 0.5	< 2	>15.00	0.5	19	7	33	3.69	< 10	< 1	0.01	< 10	10.10	3450	< 1
T 26038	201	238	0.30	< 0.2	15	220	< 0.5	< 2	>15.00	< 0.5	12	3	15	4.36	< 10	< 1	0.01	< 10	8.97	4670	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. :2-A
Tot. Pages: 6
Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26039	201 238	0.35	0.2	< 5	180	< 0.5	< 2	15.00	< 0.5	12	4	14	4.33	< 10	< 1	0.02	< 10	9.04	5050	< 1
T 26040	201 238	0.36	0.4	< 5	1140	< 0.5	< 2	14.20	< 0.5	13	7	22	4.38	< 10	< 1	0.02	< 10	8.56	5090	< 1
T 26041	201 238	0.13	< 0.2	5	100	< 0.5	< 2	>15.00	< 0.5	8	2	7	3.07	< 10	< 1	< 0.01	< 10	9.88	3860	< 1
T 26042	201 238	0.15	0.2	< 5	60	< 0.5	< 2	>15.00	< 0.5	9	< 1	6	3.13	< 10	< 1	0.01	< 10	9.57	4120	< 1
T 26043	201 238	0.33	< 0.2	30	300	< 0.5	< 2	13.80	< 0.5	11	3	14	3.99	< 10	< 1	0.01	< 10	8.28	4870	< 1
T 26044	201 238	0.64	0.2	< 5	240	< 0.5	< 2	12.80	0.5	13	10	25	4.51	< 10	< 1	0.04	< 10	7.80	4500	< 1
T 26045	201 238	0.68	0.6	10	3960	< 0.5	4	8.72	< 0.5	18	10	64	6.70	< 10	< 1	0.03	< 10	5.40	6120	< 1
T 26046	201 238	1.07	0.2	< 5	320	< 0.5	< 2	8.65	0.5	13	18	29	5.60	< 10	< 1	0.05	< 10	5.27	5480	< 1
T 26047	201 238	0.90	< 0.2	10	230	< 0.5	< 2	10.05	< 0.5	12	19	22	3.59	< 10	< 1	0.05	< 10	6.23	2850	< 1
T 26048	201 238	1.80	< 0.2	30	240	< 0.5	< 2	1.33	< 0.5	13	27	35	6.51	< 10	< 1	0.10	10	0.79	4130	< 1
T 26049	201 238	2.67	0.2	20	230	< 0.5	< 2	0.27	< 0.5	7	38	12	3.42	< 10	< 1	0.08	20	0.60	425	< 1
T 26050	201 238	2.27	0.4	25	290	< 0.5	< 2	0.46	< 0.5	10	35	15	4.11	< 10	< 1	0.09	20	0.65	680	< 1
T 26051	201 238	2.10	0.2	30	210	< 0.5	< 2	0.26	< 0.5	14	29	28	4.01	< 10	2	0.14	20	0.58	1375	< 1
T 26052	201 238	2.72	< 0.2	15	270	< 0.5	< 2	0.26	< 0.5	14	39	21	4.41	< 10	< 1	0.13	20	0.67	960	1
T 26053	201 238	2.58	0.2	< 5	230	< 0.5	< 2	0.24	< 0.5	7	40	13	3.54	< 10	< 1	0.12	20	0.66	390	< 1
T 26054	201 238	2.30	0.4	10	290	< 0.5	< 2	0.23	< 0.5	7	37	11	3.44	< 10	< 1	0.10	20	0.56	395	< 1
T 26055	201 238	2.53	0.4	20	280	< 0.5	< 2	0.28	< 0.5	8	38	19	3.87	< 10	< 1	0.11	20	0.61	465	1
T 26056	201 238	1.91	< 0.2	35	200	< 0.5	< 2	0.17	< 0.5	9	28	15	3.34	< 10	2	0.12	20	0.41	885	1
T 26057	201 238	1.98	0.4	20	330	< 0.5	4	0.60	< 0.5	12	29	46	5.53	< 10	< 1	0.12	30	0.61	2440	1
T 26058	201 238	0.71	0.8	75	260	< 0.5	< 2	0.33	< 0.5	21	9	110	7.22	< 10	< 1	0.12	20	0.61	1440	1

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. :1-B
Tot. Pages: 6
Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 25949	201 238	0.01	61	560	132	10	5	12	0.02	< 10	< 10	25	20	426
T 25950	201 238	0.01	25	1020	72	< 5	6	15	0.05	< 10	< 10	61	< 10	206
T 26001	201 238	0.01	19	800	26	< 5	3	16	0.06	< 10	< 10	66	< 10	132
T 26002	201 238	0.01	17	1380	48	< 5	3	16	0.04	< 10	< 10	50	< 10	274
T 26003	201 238	0.01	16	470	152	< 5	2	16	0.06	< 10	< 10	56	< 10	220
T 26004	201 238	0.02	32	830	2670	5	7	24	0.08	< 10	< 10	51	10	2530
T 26005	201 238	0.01	27	700	1415	5	7	17	0.06	< 10	< 10	42	< 10	1250
T 26006	201 238	0.01	24	590	224	< 5	3	16	0.05	< 10	< 10	53	< 10	274
T 26007	201 238	0.01	24	650	50	< 5	4	19	0.07	< 10	< 10	63	< 10	162
T 26008	201 238	0.01	18	450	18	< 5	3	18	0.07	< 10	< 10	64	< 10	130

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. :2-B
Tot. P :6
Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26039	201	238	0.02	12	200	12	5	1	18	0.01	< 10	< 10	9	< 10	94
T 26040	201	238	0.01	22	240	4	< 5	1	23	0.01	< 10	< 10	10	< 10	148
T 26041	201	238	0.01	7	50	< 2	5	1	14	< 0.01	< 10	< 10	4	< 10	56
T 26042	201	238	0.02	9	90	< 2	5	1	14	< 0.01	< 10	< 10	4	< 10	62
T 26043	201	238	0.02	20	220	8	5	1	14	0.01	< 10	< 10	9	< 10	118
T 26044	201	238	0.01	29	250	28	5	3	20	0.02	< 10	< 10	20	< 10	138
T 26045	201	238	0.01	50	300	52	5	3	68	0.02	< 10	< 10	26	< 10	276
T 26046	201	238	0.01	23	560	34	5	4	18	0.03	< 10	< 10	30	< 10	168
T 26047	201	238	0.01	19	300	22	5	3	19	0.04	< 10	< 10	26	< 10	106
T 26048	201	238	0.01	26	1390	100	5	5	17	0.05	< 10	< 10	46	< 10	332
T 26049	201	238	0.01	22	400	30	< 5	4	20	0.09	< 10	< 10	69	< 10	82
T 26050	201	238	0.01	25	780	54	< 5	6	19	0.08	< 10	< 10	59	< 10	132
T 26051	201	238	0.01	31	460	150	< 5	5	17	0.06	< 10	< 10	51	< 10	260
T 26052	201	238	0.01	27	580	62	< 5	5	19	0.08	< 10	< 10	71	< 10	146
T 26053	201	238	0.01	22	480	68	< 5	4	20	0.08	< 10	< 10	68	< 10	150
T 26054	201	238	0.01	19	500	64	< 5	3	19	0.07	< 10	< 10	70	< 10	136
T 26055	201	238	0.01	30	660	42	5	5	18	0.07	< 10	< 10	65	< 10	130
T 26056	201	238	0.01	14	520	82	< 5	3	14	0.05	< 10	< 10	58	< 10	146
T 26057	201	238	0.01	39	1140	72	5	5	19	0.03	< 10	< 10	50	< 10	242
T 26058	201	238	< 0.01	103	1780	40	15	4	106	< 0.01	< 10	< 10	22	< 10	260
T 26059	201	238	0.01	25	680	54	5	5	21	0.08	< 10	< 10	69	< 10	126
T 26060	201	238	0.01	20	470	42	< 5	3	18	0.07	< 10	< 10	61	< 10	122
T 26061	201	238	0.01	12	430	30	5	3	18	0.09	< 10	< 10	81	< 10	76
T 26062	201	238	0.01	24	510	28	< 5	3	17	0.06	< 10	< 10	59	< 10	102
T 26063	201	238	0.01	33	720	24	< 5	5	24	0.08	< 10	< 10	69	< 10	116
T 26064	201	238	0.01	63	1080	50	5	1	8	0.01	< 10	< 10	39	< 10	198
T 26065	201	238	0.01	26	610	52	5	7	18	0.05	< 10	< 10	49	< 10	162
T 26066	201	238	0.01	22	940	22	5	6	15	0.06	< 10	< 10	55	< 10	102
T 26067	201	238	0.01	37	1360	24	5	3	33	0.02	< 10	< 10	31	< 10	94
T 26068	201	238	0.01	24	990	24	< 5	6	15	0.06	< 10	< 10	59	< 10	220
T 26069	201	238	0.01	48	1510	30	< 5	5	30	0.04	< 10	< 10	50	< 10	128
T 26070	201	238	0.01	26	240	18	5	2	46	0.02	< 10	< 10	15	< 10	110
T 26071	201	238	0.01	42	150	8	10	2	46	< 0.01	< 10	< 10	13	< 10	136
T 26072	201	238	0.01	19	230	< 2	5	1	15	0.01	< 10	< 10	10	< 10	96
T 26073	201	238	0.01	25	190	12	10	1	20	0.01	< 10	< 10	10	< 10	104
T 26074	201	238	0.01	34	220	10	10	1	35	0.01	< 10	< 10	12	10	110
T 26075	201	238	0.01	18	170	20	5	1	27	0.01	< 10	< 10	10	< 10	140
T 26076	201	238	0.02	5	70	8	5	1	14	< 0.01	< 10	< 10	4	< 10	60
T 26077	201	238	0.02	29	160	42	5	1	23	0.01	< 10	< 10	12	< 10	112
T 26078	201	238	0.02	8	70	30	10	1	17	< 0.01	< 10	< 10	7	< 10	76

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
316 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26079	201	238	0.19	< 0.2	< 5	80	< 0.5	< 2	>15.00	< 0.5	9	1	33	3.12	< 10	1	0.02	< 10	10.00	3510	< 1
T 26080	201	238	0.49	< 0.2	35	100	< 0.5	< 2	13.60	< 0.5	14	7	26	4.26	< 10	< 1	0.03	< 10	8.18	4140	< 1
T 26081	201	238	0.18	< 0.2	25	50	< 0.5	< 2	>15.00	< 0.5	13	2	12	3.48	< 10	< 1	0.02	< 10	9.62	3960	< 1
T 26082	201	238	0.12	< 0.2	20	60	< 0.5	< 2	>15.00	< 0.5	10	3	8	2.85	< 10	< 1	0.01	< 10	9.57	3560	< 1
T 26083	201	238	0.11	< 0.2	< 5	140	< 0.5	< 2	>15.00	0.5	20	3	92	3.66	< 10	< 1	0.01	< 10	9.77	3140	< 1
T 26084	201	238	0.54	< 0.2	10	190	< 0.5	< 2	10.65	< 0.5	24	10	49	6.59	< 10	< 1	0.03	< 10	6.40	5980	< 1
T 26085	201	238	0.10	< 0.2	5	40	< 0.5	< 2	>15.00	< 0.5	12	2	29	2.71	< 10	< 1	0.01	< 10	10.35	3230	< 1
T 26086	201	238	0.38	< 0.2	25	180	< 0.5	< 2	13.40	< 0.5	21	6	43	5.05	< 10	< 1	0.02	< 10	7.96	5060	< 1
T 26087	201	238	0.27	< 0.2	< 5	170	< 0.5	< 2	>15.00	0.5	13	5	47	3.56	< 10	< 1	0.02	< 10	9.91	3850	< 1
T 26088	201	238	0.43	< 0.2	50	110	< 0.5	< 2	13.75	< 0.5	14	10	25	4.19	< 10	1	0.02	< 10	8.33	4010	< 1
T 26089	201	238	0.81	< 0.2	< 5	380	< 0.5	< 2	11.45	1.0	12	17	18	4.10	< 10	< 1	0.04	< 10	7.09	4250	< 1
T 26090	201	238	0.46	< 0.2	5	140	< 0.5	< 2	13.65	< 0.5	12	7	25	3.78	< 10	< 1	0.03	< 10	8.30	4130	< 1
T 26091	201	238	1.52	0.6	20	700	< 0.5	< 2	3.08	0.5	18	26	45	7.87	10	< 1	0.06	< 10	1.99	7230	< 1
T 26092	201	238	0.50	< 0.2	10	120	< 0.5	< 2	13.95	< 0.5	10	6	29	3.78	< 10	9	0.02	< 10	8.45	4090	< 1
T 26093	201	238	0.55	< 0.2	10	200	< 0.5	< 2	13.05	< 0.5	11	9	20	4.11	< 10	< 1	0.02	< 10	8.02	4410	< 1
T 26094	201	238	0.84	< 0.2	15	210	< 0.5	< 2	9.93	< 0.5	12	13	31	5.54	< 10	4	0.04	< 10	6.15	5810	< 1
T 26095	201	238	0.70	< 0.2	25	300	< 0.5	< 2	11.20	< 0.5	11	11	20	4.96	< 10	< 1	0.04	< 10	6.87	5340	< 1
T 26096	201	238	0.74	0.2	15	310	< 0.5	< 2	10.10	0.5	11	10	22	5.55	< 10	4	0.03	< 10	6.23	6150	< 1
T 26097	201	238	0.31	< 0.2	10	1240	< 0.5	< 2	14.80	< 0.5	11	3	35	3.31	< 10	< 1	0.02	< 10	9.11	3610	1
T 26098	201	238	0.79	< 0.2	30	890	< 0.5	< 2	8.25	0.5	14	13	70	6.36	< 10	< 1	0.03	< 10	5.11	6940	< 1
T 26099	201	238	1.10	0.2	15	1490	< 0.5	< 2	5.45	< 0.5	21	18	104	6.91	10	3	0.05	< 10	3.47	6640	2
T 26100	201	238	1.75	< 0.2	5	180	< 0.5	< 2	0.76	< 0.5	10	29	25	4.92	10	< 1	0.08	20	0.71	1965	< 1
T 26101	201	238	2.18	0.4	45	250	< 0.5	< 2	0.55	< 0.5	9	30	17	5.19	10	< 1	0.08	20	0.55	1920	< 1
T 26102	201	238	0.58	0.4	25	130	< 0.5	< 2	0.26	< 0.5	13	7	63	2.84	< 10	< 1	0.14	30	0.12	495	9
T 26103	201	238	1.68	0.2	15	270	< 0.5	< 2	0.31	< 0.5	9	26	30	4.24	10	< 1	0.14	20	0.46	1070	2
T 26104	201	238	1.60	0.2	20	190	< 0.5	< 2	0.12	< 0.5	8	28	19	3.19	10	5	0.12	20	0.35	705	2
T 26105	201	238	1.67	0.4	5	2290	< 0.5	< 2	0.49	< 0.5	11	25	24	3.96	10	1	0.11	20	0.58	1615	1
T 26106	201	238	1.68	0.2	< 5	370	< 0.5	< 2	0.26	0.5	9	25	13	3.00	10	< 1	0.14	20	0.38	800	2
T 26107	201	238	0.83	0.4	< 5	210	< 0.5	< 2	9.61	0.5	13	14	26	4.59	< 10	< 1	0.07	< 10	5.88	4440	< 1
T 26108	201	238	0.98	0.4	10	270	< 0.5	< 2	3.76	0.5	14	11	49	3.50	< 10	1	0.14	< 10	2.22	1345	3
T 26109	201	238	1.66	0.6	15	150	< 0.5	< 2	0.53	0.5	11	24	18	4.34	10	< 1	0.14	20	0.51	1670	< 1
T 26110	201	238	0.54	< 0.2	30	610	< 0.5	< 2	5.90	< 0.5	14	9	58	4.50	< 10	< 1	0.07	< 10	3.30	3630	1
T 26111	201	238	0.45	0.4	20	750	< 0.5	< 2	9.58	0.5	12	7	41	5.96	< 10	< 1	0.04	< 10	5.83	6130	< 1
T 26112	201	238	1.25	1.4	45	560	< 0.5	< 2	1.30	1.0	15	19	87	7.64	10	< 1	0.08	20	0.67	4780	1
T 26113	201	238	2.15	< 0.2	20	320	< 0.5	< 2	1.24	< 0.5	8	33	22	3.90	10	< 1	0.13	20	1.06	1040	< 1
T 26114	201	238	1.05	< 0.2	20	420	< 0.5	< 2	7.87	< 0.5	12	17	41	4.83	< 10	< 1	0.06	< 10	5.06	4150	< 1
T 26115	201	238	0.91	0.4	20	380	< 0.5	< 2	9.39	< 0.5	13	18	40	4.48	< 10	< 1	0.06	< 10	5.96	3840	< 1
T 26116	201	238	0.85	0.2	5	320	< 0.5	< 2	9.56	0.5	13	14	38	4.54	< 10	< 1	0.05	< 10	6.01	3700	< 1
T 26117	201	238	1.79	0.4	30	290	< 0.5	< 2	1.04	< 0.5	10	29	26	4.77	10	< 1	0.09	10	0.66	2290	< 1
T 26118	201	238	1.01	< 0.2	15	320	< 0.5	< 2	1.08	0.5	7	16	15	1.70	< 10	< 1	0.11	10	0.37	2170	1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To 'CHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26079	201	238	0.02	8	80	12	10	1	19	< 0.01	< 10	< 10	7	< 10	116
T 26080	201	238	0.01	16	300	28	5	2	20	0.02	< 10	< 10	17	< 10	120
T 26081	201	238	0.02	9	110	6	10	1	25	< 0.01	< 10	< 10	8	< 10	80
T 26082	201	238	0.01	6	50	12	5	1	32	< 0.01	< 10	< 10	5	< 10	62
T 26083	201	238	0.01	10	60	26	5	1	18	< 0.01	< 10	< 10	5	< 10	92
T 26084	201	238	0.01	24	590	48	10	2	20	0.01	< 10	< 10	16	10	192
T 26085	201	238	0.02	7	50	18	5	1	20	< 0.01	< 10	< 10	5	< 10	108
T 26086	201	238	0.01	23	580	50	5	2	19	0.01	< 10	< 10	17	< 10	214
T 26087	201	238	0.02	23	120	82	10	1	17	0.01	< 10	< 10	12	< 10	280
T 26088	201	238	0.02	10	210	28	10	1	16	0.02	< 10	< 10	18	< 10	112
T 26089	201	238	0.02	21	400	70	5	2	16	0.04	< 10	< 10	28	< 10	162
T 26090	201	238	0.02	18	330	28	5	1	13	0.02	< 10	< 10	18	< 10	162
T 26091	201	238	0.01	39	710	118	10	4	20	0.05	< 10	< 10	50	< 10	482
T 26092	201	238	0.02	12	260	6	10	1	16	0.02	< 10	< 10	17	< 10	126
T 26093	201	238	0.02	14	270	16	5	2	15	0.02	< 10	< 10	17	< 10	124
T 26094	201	238	0.01	25	430	40	10	2	23	0.03	< 10	< 10	23	< 10	168
T 26095	201	238	0.01	20	400	36	10	2	18	0.03	< 10	< 10	21	< 10	234
T 26096	201	238	0.01	19	490	40	5	2	14	0.02	< 10	< 10	21	< 10	230
T 26097	201	238	0.01	16	190	32	5	1	19	0.01	< 10	< 10	11	< 10	184
T 26098	201	238	0.01	32	720	120	10	3	15	0.02	< 10	< 10	27	< 10	444
T 26099	201	238	0.01	53	810	48	5	4	16	0.03	< 10	< 10	35	< 10	308
T 26100	201	238	0.01	23	700	2	5	5	15	0.06	< 10	< 10	48	< 10	124
T 26101	201	238	0.01	23	1220	26	< 5	3	16	0.04	< 10	< 10	52	< 10	122
T 26102	201	238	< 0.01	47	830	16	< 5	3	30	< 0.01	< 10	< 10	22	< 10	90
T 26103	201	238	0.01	32	1170	20	< 5	4	19	0.04	< 10	< 10	56	< 10	112
T 26104	201	238	0.01	21	920	18	5	1	15	0.03	< 10	< 10	54	< 10	126
T 26105	201	238	0.01	33	580	60	5	4	21	0.04	< 10	< 10	46	< 10	334
T 26106	201	238	0.01	17	470	46	< 5	3	20	0.05	< 10	< 10	56	< 10	138
T 26107	201	238	0.01	26	860	36	5	2	18	0.02	< 10	< 10	22	< 10	282
T 26108	201	238	0.01	32	1180	72	5	2	42	0.02	< 10	< 10	19	< 10	734
T 26109	201	238	0.01	20	890	468	5	5	23	0.05	< 10	< 10	44	< 10	620
T 26110	201	238	0.01	35	1010	102	5	3	33	0.01	< 10	< 10	19	< 10	320
T 26111	201	238	0.01	24	940	96	5	2	16	0.01	< 10	< 10	16	< 10	396
T 26112	201	238	0.01	55	1430	254	10	5	16	0.03	< 10	< 10	39	< 10	820
T 26113	201	238	0.01	23	610	118	< 5	3	18	0.05	< 10	< 10	52	< 10	266
T 26114	201	238	0.01	26	600	86	5	3	21	0.04	< 10	< 10	31	< 10	234
T 26115	201	238	0.02	24	540	82	5	3	23	0.03	< 10	< 10	28	< 10	236
T 26116	201	238	0.01	20	580	74	10	3	23	0.03	< 10	< 10	25	< 10	214
T 26117	201	238	0.01	26	1330	60	< 5	5	18	0.05	< 10	< 10	49	< 10	214
T 26118	201	238	0.01	12	1280	14	< 5	1	15	0.04	< 10	< 10	34	< 10	152

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To 'RCHER CATHRO & ASSOC. (1981) LTD.
016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date :28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26119	201	238	1.67	0.4	25	510	< 0.5	< 2	3.70	< 0.5	17	28	58	7.05	10	< 1	0.08	< 10	2.35	5850	< 1
T 26120	201	238	1.49	0.6	15	540	< 0.5	< 2	4.55	1.0	18	24	58	7.03	10	< 1	0.07	< 10	3.02	6850	< 1
T 26121	201	238	1.29	0.2	45	470	< 0.5	< 2	4.92	< 0.5	16	20	48	8.56	10	< 1	0.07	< 10	3.18	9160	< 1
T 26122	201	238	1.46	0.2	< 5	490	< 0.5	< 2	4.86	1.0	14	25	43	7.98	10	< 1	0.08	< 10	3.16	8350	< 1
T 26123	201	238	1.22	0.6	< 5	530	< 0.5	< 2	5.75	1.0	15	20	37	6.62	10	< 1	0.07	< 10	3.69	6540	< 1
T 26124	201	238	0.99	0.4	20	320	< 0.5	< 2	9.06	< 0.5	15	18	35	4.80	< 10	< 1	0.06	< 10	5.75	4490	< 1
T 26125	201	238	0.29	< 0.2	< 5	200	< 0.5	< 2	>15.00	0.5	9	5	16	3.37	< 10	< 1	0.02	< 10	9.61	3880	< 1
T 26126	201	238	0.32	< 0.2	10	150	< 0.5	< 2	>15.00	< 0.5	12	6	18	3.23	< 10	< 1	0.02	< 10	9.86	3420	< 1
T 26127	201	238	0.42	< 0.2	15	330	< 0.5	< 2	14.40	< 0.5	11	6	22	3.49	< 10	< 1	0.01	< 10	8.95	3550	< 1
T 26128	201	238	0.73	< 0.2	35	220	< 0.5	< 2	10.50	< 0.5	13	10	67	6.63	< 10	< 1	0.02	< 10	6.60	7330	< 1
T 26129	201	238	0.56	0.2	< 5	180	< 0.5	< 2	11.65	1.5	12	8	43	5.18	< 10	< 1	0.01	< 10	7.21	5530	< 1
T 26130	201	238	0.96	0.2	5	180	< 0.5	< 2	7.51	1.0	15	16	55	6.05	< 10	< 1	0.03	< 10	4.74	5790	< 1
T 26131	201	238	0.55	0.4	35	130	< 0.5	< 2	11.05	< 0.5	25	9	40	6.29	< 10	< 1	0.02	< 10	6.88	5880	< 1
T 26132	201	238	0.21	1.6	65	270	< 0.5	< 2	11.70	< 0.5	50	2	94	5.79	< 10	< 1	0.03	< 10	7.08	4040	< 1
T 26133	201	238	0.11	0.2	30	60	< 0.5	< 2	>15.00	< 0.5	18	1	37	3.10	< 10	< 1	< 0.01	< 10	10.15	3130	< 1
T 26134	201	238	0.32	0.6	85	500	< 0.5	< 2	13.30	< 0.5	22	4	77	5.71	< 10	< 1	0.02	< 10	8.07	4780	< 1
T 26146	201	238	1.76	0.2	65	210	< 0.5	< 2	0.44	< 0.5	20	28	55	8.73	10	< 1	0.13	30	0.45	5370	1
T 26147	201	238	1.98	< 0.2	30	200	< 0.5	< 2	0.52	< 0.5	6	30	17	6.68	10	< 1	0.09	20	0.49	2570	< 1
T 26148	201	238	2.22	0.6	35	180	< 0.5	< 2	0.29	< 0.5	13	30	21	4.00	10	< 1	0.08	20	0.58	970	< 1
T 26149	201	238	2.15	0.6	25	200	< 0.5	< 2	0.48	< 0.5	10	32	17	4.51	10	< 1	0.11	20	0.60	825	< 1
T 26150	201	238	2.21	< 0.2	15	240	< 0.5	< 2	0.33	< 0.5	6	35	10	4.43	10	1	0.10	20	0.56	930	< 1
T 26151	201	238	2.33	< 0.2	45	260	< 0.5	< 2	0.38	< 0.5	10	33	15	7.46	10	< 1	0.09	20	0.47	3790	< 1
T 26152	201	238	2.11	< 0.2	10	190	< 0.5	< 2	0.24	< 0.5	7	33	12	4.21	10	< 1	0.09	20	0.56	830	< 1
T 26153	201	238	2.24	0.2	40	200	< 0.5	< 2	0.19	< 0.5	8	33	15	3.24	10	< 1	0.11	20	0.55	510	< 1
T 26154	201	238	2.06	0.2	5	150	< 0.5	< 2	0.20	< 0.5	7	30	15	3.08	< 10	< 1	0.13	20	0.62	210	< 1
T 26155	201	238	2.02	< 0.2	< 5	200	< 0.5	< 2	0.23	< 0.5	10	31	17	3.46	10	< 1	0.10	20	0.57	830	< 1
T 26156	201	238	2.09	0.2	20	190	< 0.5	< 2	0.22	< 0.5	11	33	20	3.36	10	< 1	0.11	20	0.60	710	< 1
T 26157	201	238	1.60	0.2	15	160	< 0.5	< 2	0.27	< 0.5	13	22	22	5.21	10	< 1	0.13	20	0.49	1445	< 1
T 26158	201	238	1.34	0.6	40	240	< 0.5	< 2	1.92	< 0.5	20	16	45	4.86	10	< 1	0.24	10	1.54	2250	< 1
T 26159	201	238	2.45	0.4	5	190	< 0.5	< 2	0.20	< 0.5	9	34	12	3.63	10	< 1	0.11	20	0.59	445	< 1
T 26160	201	238	2.52	0.2	< 5	190	< 0.5	< 2	0.20	< 0.5	7	34	9	3.53	10	< 1	0.09	20	0.56	335	1
T 26161	201	238	2.48	0.2	15	200	< 0.5	< 2	0.20	< 0.5	10	38	14	3.50	10	< 1	0.10	20	0.55	515	1
T 26162	201	238	1.82	0.2	< 5	160	< 0.5	< 2	0.14	< 0.5	8	28	13	3.27	10	< 1	0.11	20	0.40	715	1
T 26163	201	238	1.02	< 0.2	10	170	< 0.5	< 2	4.28	0.5	15	16	29	3.74	< 10	< 1	0.10	< 10	2.93	2200	< 1
T 26164	201	238	1.72	< 0.2	30	230	< 0.5	< 2	0.43	< 0.5	12	27	22	4.06	10	< 1	0.09	20	0.52	1360	1
T 26165	201	238	1.35	0.6	10	160	< 0.5	< 2	2.18	1.0	14	24	30	4.67	10	< 1	0.07	< 10	1.39	1965	< 1
T 26166	201	238	2.18	0.4	35	210	< 0.5	< 2	0.59	< 0.5	10	32	14	3.44	10	< 1	0.09	20	0.64	635	1
T 26167	201	238	2.03	0.4	10	230	< 0.5	< 2	0.93	< 0.5	12	31	17	4.11	10	< 1	0.11	20	0.78	1425	< 1
T 26168	201	238	2.05	0.8	10	210	< 0.5	< 2	0.51	< 0.5	11	34	19	4.05	10	< 1	0.12	20	0.69	615	1
T 26169	201	238	2.32	0.4	10	260	< 0.5	< 2	0.47	< 0.5	9	37	14	3.63	10	< 1	0.12	20	0.66	560	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To : ARCHER CATHRO & ASSOC. (1981) LTD.
016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No :4-B
Tot. P 6
Date 28-AUG-89
Invoice # :I-8923492
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26119	201	238	0.01	36	1160	64	10	5	18	0.05	< 10	< 10	51	< 10	462
T 26120	201	238	0.01	37	790	80	5	4	20	0.05	< 10	< 10	47	< 10	538
T 26121	201	238	0.01	30	760	36	10	4	16	0.05	< 10	< 10	36	< 10	302
T 26122	201	238	0.01	26	810	36	10	4	16	0.05	< 10	< 10	39	< 10	308
T 26123	201	238	0.01	27	720	62	5	3	16	0.04	< 10	< 10	33	< 10	302
T 26124	201	238	0.01	22	420	22	5	3	16	0.04	< 10	< 10	29	< 10	182
T 26125	201	238	0.01	11	180	94	5	1	15	0.01	< 10	< 10	11	< 10	100
T 26126	201	238	0.02	16	160	98	10	1	25	0.01	< 10	< 10	13	< 10	92
T 26127	201	238	0.02	11	200	6	5	1	15	0.02	< 10	< 10	16	< 10	100
T 26128	201	238	0.01	28	510	54	10	2	14	0.02	< 10	< 10	25	< 10	224
T 26129	201	238	0.01	16	350	14	5	2	16	0.02	< 10	< 10	21	< 10	218
T 26130	201	238	0.01	33	520	48	5	3	17	0.03	< 10	< 10	34	< 10	304
T 26131	201	238	0.01	30	340	48	10	2	15	0.02	< 10	< 10	25	< 10	226
T 26132	201	238	0.01	68	470	238	15	1	41	< 0.01	10	< 10	8	< 10	408
T 26133	201	238	0.01	12	80	84	5	1	17	< 0.01	< 10	< 10	6	< 10	168
T 26134	201	238	0.01	21	420	124	5	2	20	0.01	< 10	< 10	13	< 10	412
T 26146	201	238	0.01	48	900	66	5	8	15	0.04	< 10	< 10	51	< 10	338
T 26147	201	238	0.01	22	1020	24	< 5	5	14	0.05	< 10	< 10	52	< 10	354
T 26148	201	238	0.01	29	660	94	< 5	4	14	0.06	< 10	< 10	53	< 10	278
T 26149	201	238	0.01	20	980	58	< 5	6	16	0.06	< 10	< 10	53	< 10	316
T 26150	201	238	0.01	17	680	24	< 5	3	18	0.08	< 10	< 10	71	< 10	136
T 26151	201	238	0.01	19	1200	24	< 5	4	15	0.06	< 10	< 10	71	< 10	192
T 26152	201	238	0.01	18	730	96	< 5	3	14	0.06	< 10	< 10	57	< 10	240
T 26153	201	238	0.01	20	630	54	< 5	3	17	0.06	< 10	< 10	54	< 10	168
T 26154	201	238	0.01	21	650	74	< 5	4	14	0.05	< 10	< 10	41	< 10	174
T 26155	201	238	0.01	22	590	70	< 5	3	16	0.06	< 10	< 10	52	< 10	192
T 26156	201	238	0.01	26	580	70	< 5	4	18	0.07	< 10	< 10	52	< 10	174
T 26157	201	238	0.01	21	860	322	< 5	5	13	0.03	< 10	< 10	35	< 10	428
T 26158	201	238	0.01	29	660	224	5	7	14	0.02	< 10	< 10	22	< 10	470
T 26159	201	238	0.01	24	400	56	< 5	4	16	0.08	< 10	< 10	61	< 10	158
T 26160	201	238	0.01	18	330	46	< 5	3	16	0.08	< 10	< 10	62	< 10	114
T 26161	201	238	0.01	24	380	206	< 5	4	18	0.08	< 10	< 10	67	< 10	260
T 26162	201	238	0.01	15	370	92	< 5	3	14	0.06	< 10	< 10	57	< 10	200
T 26163	201	238	0.01	27	680	322	< 5	6	24	0.03	< 10	< 10	29	< 10	558
T 26164	201	238	0.01	24	1080	76	< 5	5	16	0.04	< 10	< 10	42	< 10	270
T 26165	201	238	0.01	25	1110	324	5	5	21	0.03	< 10	< 10	45	< 10	898
T 26166	201	238	0.01	16	650	68	< 5	4	18	0.05	< 10	< 10	51	< 10	260
T 26167	201	238	0.01	21	1030	102	< 5	5	16	0.05	< 10	< 10	50	< 10	288
T 26168	201	238	0.01	25	650	200	< 5	7	20	0.07	< 10	< 10	54	< 10	470
T 26169	201	238	0.01	20	860	78	< 5	5	19	0.07	< 10	< 10	58	< 10	258

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No : 5-A
Tot. P : 6
Date : 28-AUG-89
Invoice # : I-8923492
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE	Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26170	201 238	2.15	0.4	35	200	< 0.5	< 2	0.29	< 0.5	9	29	17	4.22	< 10	< 1	0.16	20	0.55	960	< 1
T 26171	201 238	2.35	0.4	10	210	< 0.5	< 2	0.43	< 0.5	9	36	12	3.62	< 10	< 1	0.16	20	0.66	435	< 1
T 26172	201 238	2.41	0.2	< 5	270	< 0.5	< 2	0.28	< 0.5	8	34	11	3.34	< 10	< 1	0.13	20	0.59	450	< 1
T 26173	201 238	2.61	0.2	5	250	< 0.5	< 2	0.35	< 0.5	7	38	9	3.62	< 10	< 1	0.08	20	0.61	440	< 1
T 26174	201 238	2.63	0.6	10	260	< 0.5	< 2	0.44	< 0.5	7	37	11	3.98	< 10	< 1	0.11	20	0.63	495	< 1
T 26175	201 238	2.45	0.2	10	260	< 0.5	< 2	0.34	< 0.5	8	36	14	3.90	< 10	< 1	0.13	20	0.61	715	< 1
T 26176	201 238	2.78	0.4	20	320	< 0.5	< 2	0.42	< 0.5	5	38	8	3.04	< 10	< 1	0.14	20	0.66	245	< 1
T 26177	201 238	1.63	0.6	25	300	< 0.5	< 2	0.88	0.5	14	29	69	7.58	< 10	< 1	0.10	20	0.48	4360	< 1
T 26178	201 238	1.60	0.6	25	210	< 0.5	< 2	1.11	0.5	12	28	27	4.94	< 10	< 1	0.09	10	0.55	2310	< 1
T 26179	201 238	1.46	< 0.2	50	730	< 0.5	< 2	1.86	< 0.5	14	24	29	4.05	< 10	< 1	0.16	10	1.40	2020	< 1
T 26180	201 238	1.75	0.2	5	240	< 0.5	< 2	0.20	< 0.5	8	29	17	3.51	< 10	< 1	0.12	20	0.45	940	< 1
T 26181	201 238	2.32	0.2	20	270	< 0.5	< 2	0.25	< 0.5	5	36	12	3.78	< 10	< 1	0.10	20	0.60	545	< 1
T 26182	201 238	2.12	< 0.2	25	170	< 0.5	< 2	0.15	< 0.5	9	31	21	4.12	< 10	< 1	0.11	20	0.53	1090	< 1
T 26183	201 238	2.56	1.0	40	280	< 0.5	< 2	0.49	< 0.5	15	35	35	5.52	< 10	< 1	0.19	30	0.65	2210	< 1
T 26184	201 238	1.57	1.2	35	850	< 0.5	< 2	0.68	0.5	16	24	56	6.92	< 10	< 1	0.13	20	0.50	2770	< 1
T 26185	201 238	2.24	0.8	15	220	< 0.5	< 2	0.23	< 0.5	6	35	18	3.56	< 10	< 1	0.12	20	0.54	670	< 1
T 26186	201 238	2.41	0.4	35	170	< 0.5	< 2	0.17	< 0.5	6	36	17	3.56	< 10	< 1	0.15	20	0.58	495	1
T 26187	201 238	2.00	0.4	15	150	< 0.5	< 2	0.23	< 0.5	8	33	16	3.05	< 10	< 1	0.11	20	0.60	390	< 1
T 26188	201 238	2.09	0.8	5	170	< 0.5	< 2	0.22	< 0.5	8	31	25	3.75	< 10	< 1	0.15	30	0.62	565	< 1
T 26189	201 238	2.20	0.4	< 5	210	< 0.5	< 2	0.25	0.5	5	34	17	4.04	< 10	< 1	0.14	20	0.57	715	< 1
T 26190	201 238	2.52	0.2	35	260	< 0.5	< 2	0.49	< 0.5	11	40	21	4.74	< 10	< 1	0.16	30	0.72	1165	< 1
T 26191	201 238	2.19	< 0.2	10	190	< 0.5	< 2	0.27	< 0.5	8	34	14	3.66	< 10	< 1	0.08	20	0.63	480	< 1
T 26192	201 238	2.21	0.2	40	220	< 0.5	< 2	0.32	< 0.5	11	33	24	4.12	< 10	< 1	0.09	20	0.71	995	< 1
T 26193	201 238	1.54	0.4	55	130	< 0.5	< 2	0.79	< 0.5	16	24	43	8.58	< 10	< 1	0.08	20	0.58	4960	3
T 26194	201 238	0.78	< 0.2	75	130	< 0.5	< 2	9.60	< 0.5	13	11	18	5.44	< 10	< 1	0.06	< 10	6.12	5460	1
T 26195	201 238	2.01	0.4	50	200	< 0.5	< 2	0.45	< 0.5	14	33	37	6.05	< 10	< 1	0.09	30	0.66	3070	1
T 26196	201 238	0.73	< 0.2	30	90	< 0.5	< 2	8.74	< 0.5	12	12	28	4.19	< 10	< 1	0.04	< 10	5.64	3390	3
T 26197	201 238	1.66	0.2	25	210	< 0.5	< 2	1.50	< 0.5	13	26	20	6.35	< 10	< 1	0.05	10	1.20	4710	1
T 26198	201 238	2.01	< 0.2	30	160	< 0.5	< 2	0.39	< 0.5	10	32	14	5.20	< 10	< 1	0.07	20	0.52	1405	< 1
T 26199	201 238	1.51	< 0.2	30	120	< 0.5	< 2	0.26	< 0.5	11	24	25	3.97	< 10	< 1	0.08	20	0.47	1290	< 1
T 26200	201 238	0.92	0.2	60	150	< 0.5	< 2	6.72	< 0.5	14	15	30	6.89	< 10	< 1	0.04	< 10	4.33	6080	1
T 26201	201 238	1.94	< 0.2	45	190	< 0.5	< 2	0.64	< 0.5	12	31	25	5.37	< 10	< 1	0.07	20	0.69	3070	1
T 26202	201 238	1.82	0.4	65	240	< 0.5	< 2	0.52	< 0.5	22	23	60	9.25	< 10	< 1	0.12	40	0.67	6210	2
T 26203	201 238	0.99	1.6	85	220	< 0.5	< 2	2.83	2.0	26	15	117	9.05	< 10	< 1	0.09	< 10	1.85	6850	< 1
T 26204	201 238	0.90	1.4	65	240	< 0.5	< 2	3.89	2.5	25	14	111	8.85	< 10	< 1	0.10	< 10	2.47	7070	< 1
T 26205	201 238	2.03	1.0	80	180	< 0.5	< 2	5.11	< 0.5	25	27	92	9.40	< 10	< 1	0.16	< 10	5.01	4980	< 1
T 26206	201 238	1.95	< 0.2	25	140	< 0.5	< 2	0.16	< 0.5	8	32	19	3.70	< 10	< 1	0.10	20	0.52	980	< 1
T 26207	201 238	1.59	< 0.2	5	120	< 0.5	< 2	0.16	< 0.5	6	26	11	2.74	< 10	< 1	0.07	10	0.45	380	< 1
T 26208	201 238	1.89	< 0.2	< 5	150	< 0.5	< 2	0.12	< 0.5	8	29	14	3.18	< 10	< 1	0.07	20	0.44	525	< 1
T 26209	201 238	2.03	< 0.2	5	190	< 0.5	< 2	0.18	< 0.5	8	31	12	3.08	< 10	< 1	0.06	20	0.56	375	< 1

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: RCHER CATHRO & ASSOC. (1981) LTD.

.016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page No : 5-B
Tot. Pgs :
Date : 28-AUG-89
Invoice # : I-8923492
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26170	201 238	0.01	20	680	104	< 5	5	14	0.05	< 10	< 10	53	< 10	280
T 26171	201 238	0.01	19	530	112	< 5	5	20	0.07	< 10	< 10	64	< 10	334
T 26172	201 238	0.01	15	360	78	< 5	4	19	0.08	< 10	< 10	64	< 10	190
T 26173	201 238	0.01	17	600	80	< 5	4	19	0.08	< 10	< 10	67	< 10	164
T 26174	201 238	0.01	21	810	150	5	5	21	0.08	< 10	< 10	71	< 10	358
T 26175	201 238	0.01	23	500	114	< 5	5	20	0.08	< 10	< 10	66	< 10	200
T 26176	201 238	0.01	17	420	60	< 5	4	23	0.09	< 10	< 10	69	< 10	138
T 26177	201 238	0.01	27	1460	248	15	8	18	0.03	< 10	< 10	56	< 10	498
T 26178	201 238	0.01	24	1560	272	5	5	21	0.04	< 10	< 10	46	< 10	672
T 26179	201 238	0.01	28	630	144	5	7	23	0.04	< 10	< 10	37	< 10	318
T 26180	201 238	0.01	24	560	56	5	4	16	0.05	< 10	< 10	46	< 10	170
T 26181	201 238	0.01	22	500	130	< 5	4	17	0.07	< 10	< 10	63	< 10	180
T 26182	201 238	0.01	25	470	62	< 5	4	14	0.06	< 10	< 10	57	< 10	166
T 26183	201 238	0.01	38	1000	118	< 5	9	16	0.05	< 10	< 10	50	< 10	298
T 26184	201 238	0.01	31	1340	404	5	6	15	0.03	< 10	< 10	37	< 10	686
T 26185	201 238	0.01	21	580	212	5	4	19	0.07	< 10	< 10	58	< 10	214
T 26186	201 238	0.01	21	580	58	< 5	4	16	0.06	< 10	< 10	58	< 10	158
T 26187	201 238	0.01	21	470	66	< 5	4	19	0.08	< 10	< 10	53	< 10	200
T 26188	201 238	0.01	23	790	132	< 5	5	16	0.05	< 10	< 10	49	< 10	338
T 26189	201 238	0.01	19	730	74	5	4	18	0.06	< 10	< 10	59	< 10	256
T 26190	201 238	0.01	28	790	68	< 5	8	23	0.09	< 10	< 10	68	< 10	322
T 26191	201 238	0.01	21	600	70	< 5	5	15	0.06	< 10	< 10	52	< 10	196
T 26192	201 238	0.01	27	670	50	5	5	17	0.07	< 10	< 10	56	< 10	162
T 26193	201 238	0.01	32	1000	116	5	7	13	0.04	< 10	< 10	47	< 10	470
T 26194	201 238	0.01	16	420	34	10	3	14	0.02	< 10	< 10	40	< 10	130
T 26195	201 238	0.01	33	500	54	5	7	13	0.06	< 10	< 10	53	< 10	234
T 26196	201 238	0.01	22	240	22	5	4	15	0.03	< 10	< 10	24	< 10	112
T 26197	201 238	0.01	30	490	30	< 5	6	14	0.05	< 10	< 10	46	< 10	138
T 26198	201 238	0.01	15	920	116	< 5	3	13	0.05	< 10	< 10	58	< 10	406
T 26199	201 238	0.01	21	480	252	< 5	4	15	0.06	< 10	< 10	52	< 10	548
T 26200	201 238	0.01	27	450	128	5	5	15	0.02	< 10	< 10	27	< 10	434
T 26201	201 238	0.01	25	680	46	5	6	15	0.05	< 10	< 10	51	< 10	480
T 26202	201 238	0.01	47	1140	158	5	9	12	0.02	< 10	< 10	41	< 10	468
T 26203	201 238	0.01	39	750	486	10	6	11	0.01	< 10	< 10	30	< 10	1940
T 26204	201 238	0.01	37	800	482	10	6	11	0.01	< 10	< 10	29	< 10	1985
T 26205	201 238	0.01	46	480	182	15	11	12	0.02	< 10	< 10	41	< 10	500
T 26206	201 238	0.01	23	480	48	< 5	3	15	0.07	< 10	< 10	53	< 10	152
T 26207	201 238	0.01	16	450	52	< 5	2	11	0.05	< 10	< 10	44	< 10	126
T 26208	201 238	0.01	19	440	38	< 5	3	12	0.05	< 10	< 10	48	< 10	122
T 26209	201 238	0.01	20	460	64	< 5	4	12	0.05	< 10	< 10	45	< 10	162

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To : ARCHER CATHRO & ASSOC. (1981) LTD.
16 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26210	201	238	2.24	0.2	< 5	230	< 0.5	6	0.24	0.5	7	35	16	3.55	< 10	< 1	0.07	20	0.64	360	< 1
T 26211	201	238	1.71	0.6	< 5	150	< 0.5	< 2	2.87	1.5	18	33	41	4.61	< 10	< 1	0.12	20	2.11	2160	< 1
T 26212	201	238	1.97	0.6	< 5	180	< 0.5	6	0.26	0.5	9	33	16	3.64	< 10	< 1	0.14	20	0.56	790	1
T 26213	201	238	1.77	0.8	< 5	260	< 0.5	8	0.29	0.5	11	33	27	3.90	< 10	< 1	0.16	30	0.56	905	2
T 26214	201	238	2.30	1.6	< 5	450	< 0.5	12	0.52	1.0	15	26	26	7.28	< 10	< 1	0.11	40	0.37	3410	< 1
T 26215	201	238	1.46	1.4	10	520	< 0.5	14	1.36	1.0	20	26	46	6.20	< 10	< 1	0.16	30	0.83	3810	4
T 26216	201	238	1.15	< 0.2	5	300	< 0.5	6	6.00	0.5	14	15	40	4.77	< 10	< 1	0.15	< 10	3.72	1925	1
T 26217	201	238	0.33	< 0.2	40	100	< 0.5	< 2	>15.00	< 0.5	13	8	43	3.72	< 10	< 1	0.05	< 10	9.17	3320	< 1
T 26218	201	238	0.34	< 0.2	5	110	< 0.5	< 2	14.60	1.0	13	13	40	3.68	< 10	< 1	0.05	< 10	8.84	3310	1
T 26219	201	238	0.23	< 0.2	5	100	< 0.5	< 2	>15.00	< 0.5	12	6	191	3.06	< 10	< 1	0.04	< 10	9.61	2880	1
T 26220	201	238	0.41	< 0.2	15	120	< 0.5	< 2	13.75	0.5	15	12	42	3.68	< 10	< 1	0.05	< 10	8.08	2930	< 1
T 26221	201	238	1.40	0.8	10	380	< 0.5	16	3.33	1.0	23	20	52	4.90	< 10	< 1	0.29	20	2.11	1665	< 1
T 26222	201	238	1.33	1.4	< 5	290	< 0.5	12	1.34	2.0	24	20	60	4.68	< 10	< 1	0.29	30	0.89	2020	4
T 26223	201	238	1.81	0.6	< 5	250	< 0.5	12	0.84	0.5	15	25	26	4.19	< 10	< 1	0.23	30	0.81	1475	2
T 26224	201	238	1.19	< 0.2	10	1170	< 0.5	14	5.26	0.5	21	17	60	4.05	< 10	< 1	0.17	< 10	3.28	1605	4
T 26225	201	238	0.20	< 0.2	5	940	< 0.5	< 2	>15.00	< 0.5	8	5	10	2.68	< 10	< 1	0.01	< 10	11.00	2580	1
T 26226	201	238	2.12	1.2	< 5	720	< 0.5	14	0.46	1.5	24	32	35	6.03	< 10	< 1	0.13	30	0.65	2910	< 1
T 26227	201	238	2.09	0.4	< 5	180	< 0.5	< 2	0.19	0.5	13	31	15	3.42	< 10	< 1	0.08	20	0.57	465	1
T 26228	201	238	2.01	0.4	10	160	< 0.5	10	0.22	< 0.5	12	35	21	3.20	< 10	< 1	0.11	20	0.57	380	< 1
T 26229	201	238	2.26	0.4	< 5	250	< 0.5	6	0.35	0.5	10	33	7	3.10	< 10	< 1	0.13	20	0.63	325	< 1
T 26230	201	238	2.47	0.8	< 5	280	< 0.5	8	0.30	< 0.5	10	38	15	3.22	< 10	< 1	0.11	30	0.60	410	< 1
T 26231	201	238	2.09	0.8	< 5	310	< 0.5	6	0.72	< 0.5	12	31	19	4.06	< 10	< 1	0.11	30	0.61	1205	< 1
T 26232	201	238	1.78	0.6	15	220	< 0.5	8	1.30	< 0.5	14	31	32	4.92	< 10	< 1	0.12	30	1.07	1965	2
T 26233	201	238	2.21	0.6	5	320	< 0.5	6	0.78	0.5	17	36	21	4.66	< 10	< 1	0.11	20	0.73	1935	< 1
T 26234	201	238	1.19	< 0.2	15	450	< 0.5	14	7.09	< 0.5	17	18	38	5.14	< 10	< 1	0.06	< 10	4.34	4060	< 1
T 26235	201	238	1.19	< 0.2	< 5	230	< 0.5	4	6.29	1.0	19	25	36	4.76	< 10	< 1	0.06	< 10	3.95	3780	< 1
T 26236	201	238	0.41	< 0.2	10	310	< 0.5	< 2	14.45	0.5	17	9	20	5.34	< 10	< 1	0.01	< 10	8.82	5810	1
T 26237	201	238	0.46	< 0.2	< 5	260	< 0.5	< 2	14.60	0.5	10	8	24	4.93	< 10	< 1	0.02	< 10	8.81	5560	2
T 26238	201	238	1.14	< 0.2	20	600	< 0.5	10	8.67	< 0.5	18	18	28	7.12	< 10	< 1	0.05	< 10	5.24	7950	< 1
T 26239	201	238	1.08	< 0.2	5	420	< 0.5	2	8.57	< 0.5	15	17	23	5.76	< 10	< 1	0.04	< 10	5.16	6100	1
T 26240	201	238	1.66	< 0.2	5	550	< 0.5	6	4.34	0.5	17	24	24	7.29	< 10	< 1	0.07	10	2.80	6900	< 1
T 26241	201	238	1.62	< 0.2	< 5	530	< 0.5	6	4.15	1.0	21	24	37	8.98	< 10	< 1	0.07	10	2.71	9500	1
T 26242	201	238	1.16	< 0.2	5	470	< 0.5	10	7.53	1.0	21	17	35	8.52	< 10	< 1	0.05	< 10	4.47	9340	< 1
T 26243	201	238	0.93	< 0.2	< 5	140	< 0.5	6	7.93	1.0	27	17	72	5.41	< 10	< 1	0.12	< 10	4.79	3720	1
T 26244	201	238	1.14	< 0.2	35	420	< 0.5	6	7.74	0.5	35	19	99	10.10	< 10	< 1	0.05	< 10	4.63	>10000	1
T 26245	201	238	1.03	< 0.2	15	430	< 0.5	2	8.49	0.5	27	20	73	8.85	< 10	< 1	0.05	< 10	5.07	9090	< 1
T 26246	201	238	0.56	< 0.2	10	160	< 0.5	< 2	14.05	< 0.5	15	15	47	6.09	< 10	< 1	0.02	< 10	8.31	6610	< 1
T 26247	201	238	1.65	1.0	35	800	< 0.5	16	2.65	0.5	34	25	119	9.99	< 10	< 1	0.09	30	1.59	9430	1
T 26248	201	238	1.56	< 0.2	20	230	< 0.5	10	4.61	0.5	16	24	22	6.51	< 10	< 1	0.08	10	2.85	5060	2
T 26249	201	238	0.67	< 0.2	25	200	< 0.5	< 2	10.90	2.5	22	11	78	5.95	< 10	< 1	0.07	< 10	6.49	5730	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To : ARCHER CATHRO & ASSOC. (1981) LTD.
16 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

CERTIFICATE OF ANALYSIS A8923492

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26210	201	238	0.01	25	550	56	< 5	5	15	0.06	< 10	< 10	49	< 10	144
T 26211	201	238	0.02	33	810	474	10	6	29	0.08	< 10	< 10	48	< 10	660
T 26212	201	238	0.01	25	460	118	< 5	3	16	0.06	< 10	< 10	57	< 10	266
T 26213	201	238	0.01	34	930	104	< 5	3	22	0.05	< 10	< 10	52	< 10	260
T 26214	201	238	0.01	25	1860	430	< 5	8	10	0.02	< 10	< 10	38	< 10	538
T 26215	201	238	0.01	38	1300	224	5	6	26	0.03	< 10	< 10	35	< 10	616
T 26216	201	238	0.01	31	740	204	15	6	33	0.03	< 10	< 10	27	< 10	438
T 26217	201	238	0.02	18	50	136	20	2	54	0.01	< 10	< 10	10	10	508
T 26218	201	238	0.02	14	130	180	15	3	54	0.01	< 10	< 10	10	10	660
T 26219	201	238	0.01	40	< 10	32	25	1	65	< 0.01	< 10	< 10	3	< 10	190
T 26220	201	238	0.02	18	240	146	20	3	50	0.01	< 10	< 10	12	10	570
T 26221	201	238	0.01	31	850	212	15	7	27	0.02	< 10	< 10	29	< 10	684
T 26222	201	238	0.01	43	1070	208	5	6	26	0.02	< 10	< 10	29	< 10	550
T 26223	201	238	0.01	19	760	132	< 5	4	20	0.04	< 10	< 10	49	< 10	314
T 26224	201	238	0.01	43	860	148	15	5	44	0.02	< 10	< 10	25	10	334
T 26225	201	238	0.02	23	< 10	36	20	1	58	< 0.01	< 10	< 10	3	10	102
T 26226	201	238	0.01	52	790	182	< 5	8	16	0.04	< 10	< 10	45	< 10	294
T 26227	201	238	0.01	20	580	76	5	4	15	0.05	< 10	< 10	52	< 10	138
T 26228	201	238	0.01	27	470	40	< 5	5	16	0.06	< 10	< 10	48	< 10	120
T 26229	201	238	0.01	17	710	32	< 5	3	20	0.07	< 10	< 10	63	< 10	114
T 26230	201	238	0.01	29	540	28	5	5	23	0.09	< 10	< 10	62	< 10	126
T 26231	201	238	0.01	17	1130	48	5	6	20	0.05	< 10	< 10	53	< 10	140
T 26232	201	238	0.02	25	740	46	< 5	7	23	0.08	< 10	< 10	52	< 10	188
T 26233	201	238	0.01	29	1230	74	< 5	6	20	0.06	< 10	< 10	59	< 10	196
T 26234	201	238	0.02	25	620	38	20	5	34	0.05	< 10	< 10	34	10	182
T 26235	201	238	0.02	26	460	66	15	5	30	0.06	< 10	< 10	34	10	170
T 26236	201	238	0.01	13	60	44	25	2	37	0.01	< 10	< 10	9	10	116
T 26237	201	238	0.02	18	150	10	25	2	40	0.01	< 10	< 10	12	10	120
T 26238	201	238	0.02	39	580	26	15	4	29	0.03	< 10	< 10	32	< 10	188
T 26239	201	238	0.02	32	500	24	15	3	30	0.03	< 10	< 10	30	10	146
T 26240	201	238	0.02	30	750	20	5	5	24	0.05	< 10	< 10	47	< 10	168
T 26241	201	238	0.01	40	810	28	5	6	23	0.04	< 10	< 10	44	< 10	228
T 26242	201	238	0.01	34	710	32	15	4	30	0.03	< 10	< 10	35	< 10	270
T 26243	201	238	0.02	30	680	280	10	8	42	0.04	< 10	< 10	36	10	710
T 26244	201	238	0.02	51	870	114	15	5	30	0.03	< 10	< 10	37	10	386
T 26245	201	238	0.01	37	700	68	20	4	33	0.03	< 10	< 10	32	< 10	310
T 26246	201	238	0.02	19	330	32	15	2	41	0.01	< 10	< 10	16	< 10	146
T 26247	201	238	0.01	39	1000	98	5	6	20	0.04	< 10	< 10	54	< 10	424
T 26248	201	238	0.01	35	600	34	5	7	23	0.04	< 10	< 10	43	< 10	298
T 26249	201	238	0.02	32	260	350	15	6	38	0.01	< 10	< 10	24	< 10	1395

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T. ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page No. :1-A
Tot. P. :4
Date :28-AUG-89
Invoice # :I-8923493
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26250	201	238	1.54	0.2	15	240	< 5.0	4	0.41	< 0.5	9	28	28	4.20	10	< 1	0.06	20	0.48	800	< 1
T 26251	201	238	1.36	0.4	20	170	< 5.0	2	0.33	< 0.5	11	25	25	4.96	10	< 1	0.05	20	0.42	1425	< 1
T 26252	201	238	1.21	< 0.2	20	150	< 5.0	2	0.19	< 0.5	7	22	22	3.37	10	< 1	0.06	10	0.37	745	< 1
T 26253	201	238	1.16	< 0.2	50	140	< 5.0	< 2	0.22	< 0.5	16	21	45	4.61	10	< 1	0.06	20	0.39	1815	< 1
T 26254	201	238	1.63	< 0.2	25	200	< 5.0	2	0.57	< 0.5	13	44	122	6.55	10	1	0.10	20	0.61	2400	< 1
T 26255	201	238	0.88	< 0.2	50	130	< 5.0	< 2	0.21	< 0.5	13	17	53	4.51	10	< 1	0.07	20	0.19	1405	1
T 26256	201	238	1.32	0.2	25	160	< 5.0	4	0.35	< 0.5	12	28	56	5.02	10	< 1	0.08	20	0.46	1300	2
T 26257	201	238	1.53	0.2	30	170	< 5.0	2	0.25	< 0.5	17	30	58	4.75	10	< 1	0.08	20	0.51	1695	1
T 26258	201	238	1.35	1.6	75	720	< 5.0	< 2	0.56	< 0.5	17	28	96	5.44	10	< 1	0.08	20	0.56	2110	< 1
T 26259	201	238	1.32	0.2	20	350	< 5.0	2	1.19	0.5	14	21	44	5.47	10	< 1	0.06	10	0.55	4000	1
T 26260	201	238	1.50	< 0.2	10	250	< 5.0	< 2	1.46	0.5	14	23	47	5.97	10	< 1	0.07	10	0.81	4480	1
T 26261	201	238	1.27	< 0.2	65	160	< 5.0	< 2	3.09	< 0.5	12	20	36	4.76	10	< 1	0.08	< 10	1.89	2460	< 1
T 26262	201	238	1.64	< 0.2	55	380	< 5.0	< 2	2.13	< 0.5	15	27	61	9.05	20	< 1	0.06	< 10	1.41	9010	< 1
T 26263	201	238	1.11	0.6	5	250	< 5.0	< 2	8.90	0.5	14	19	45	5.91	< 10	< 1	0.04	< 10	5.32	5850	< 1
T 26264	201	238	1.63	0.8	5	480	< 5.0	6	1.97	1.0	16	24	57	10.40	20	< 1	0.05	< 10	1.25	>10000	< 1
T 26265	201	238	1.34	0.8	60	390	< 5.0	2	4.76	< 0.5	17	21	78	9.37	20	< 1	0.05	< 10	2.85	9570	< 1
T 26266	201	238	0.60	1.2	20	170	< 5.0	< 2	13.00	< 0.5	14	10	53	4.51	< 10	1	0.02	< 10	7.53	4450	< 1
T 26267	201	238	1.16	1.2	40	740	< 5.0	< 2	5.58	< 0.5	16	17	72	10.05	20	< 1	0.03	< 10	3.25	>10000	< 1
T 26268	201	238	0.68	0.6	< 5	460	< 5.0	< 2	10.40	< 0.5	11	10	57	5.47	< 10	< 1	0.02	< 10	5.97	5890	< 1
T 26269	201	238	0.27	0.6	15	70	< 5.0	< 2	>15.00	< 0.5	11	3	33	3.46	< 10	< 1	< 0.01	< 10	8.80	3870	< 1
T 26270	201	238	0.45	0.6	5	90	< 0.5	< 2	13.30	< 0.5	14	9	22	3.72	< 10	< 1	0.02	< 10	7.66	3790	< 1
T 26271	201	238	0.36	0.8	50	100	< 0.5	< 2	14.70	< 0.5	16	7	46	4.74	< 10	< 1	0.02	< 10	8.37	4360	1
T 26272	201	238	0.30	1.2	70	180	< 0.5	< 2	14.05	1.5	20	6	68	5.33	< 10	< 1	0.01	< 10	7.96	4920	5
T 26273	201	238	0.43	1.8	60	540	0.5	6	0.89	< 0.5	14	5	107	3.74	10	< 1	0.08	30	0.20	1495	12
T 26274	201	238	0.37	1.4	80	360	< 0.5	4	0.66	< 0.5	15	6	97	4.03	10	< 1	0.08	30	0.21	1710	17
T 26275	201	238	0.78	1.8	55	490	< 0.5	4	0.97	< 0.5	16	14	97	5.42	10	< 1	0.06	20	0.38	2870	9
T 26276	201	238	1.27	1.0	45	250	< 0.5	2	0.66	< 0.5	13	21	55	4.65	10	< 1	0.09	20	0.50	1620	7
T 26277	201	238	1.42	1.8	55	360	< 0.5	2	0.93	< 0.5	21	24	80	7.00	20	< 1	0.08	20	0.57	4520	6
T 26278	201	238	1.46	0.8	100	360	< 0.5	2	0.96	< 0.5	17	26	57	8.14	20	< 1	0.07	20	0.63	6050	< 1
T 26279	201	238	0.99	0.8	30	190	< 0.5	< 2	8.16	< 0.5	16	19	31	5.55	10	< 1	0.04	< 10	4.78	5000	< 1
T 26280	201	238	1.38	0.6	110	640	< 0.5	< 2	3.70	< 0.5	15	21	44	9.38	20	< 1	0.05	< 10	2.16	9140	< 1
T 26281	201	238	0.94	0.8	30	350	< 0.5	< 2	7.70	< 0.5	13	17	36	6.94	10	< 1	0.03	< 10	4.49	7100	< 1
T 26282	201	238	0.92	0.8	65	310	< 0.5	< 2	8.11	< 0.5	14	15	42	5.93	10	< 1	0.03	< 10	4.77	5690	< 1
T 26283	201	238	1.13	0.2	30	230	0.5	< 2	0.64	< 0.5	14	19	46	3.61	10	< 1	0.08	30	0.40	900	1
T 26284	201	238	1.16	0.4	50	190	< 0.5	< 2	1.12	< 0.5	11	19	57	4.31	10	< 1	0.08	20	0.62	1735	1
T 26285	201	238	1.13	0.2	55	140	< 0.5	4	0.38	< 0.5	11	22	45	4.48	10	< 1	0.07	30	0.35	880	1
T 26286	201	238	1.25	0.6	60	120	< 0.5	2	0.67	< 0.5	16	29	89	6.05	10	< 1	0.07	20	0.35	1855	< 1
T 26287	201	238	1.34	< 0.2	25	170	< 0.5	< 2	0.26	< 0.5	10	28	44	4.13	10	< 1	0.08	10	0.37	1155	< 1
T 26288	201	238	1.60	< 0.2	25	220	< 0.5	2	0.20	< 0.5	13	32	37	4.59	10	< 1	0.07	20	0.47	1490	< 1
T 26289	201	238	1.04	< 0.2	15	130	< 0.5	2	0.09	< 0.5	5	22	20	3.64	10	< 1	0.07	10	0.14	755	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T. 'RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page N : 1-B
Tot. P : 4
Date : 28-AUG-89
Invoice # : I-8923493
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26250	201 238	0.01	24	1130	34	5	4	16	0.03	< 10	< 10	46	< 10	220
T 26251	201 238	0.01	22	860	54	5	8	13	0.03	< 10	< 10	42	< 10	160
T 26252	201 238	0.01	17	790	30	5	3	13	0.03	< 10	< 10	41	< 10	134
T 26253	201 238	0.01	31	680	66	5	6	13	0.03	< 10	< 10	36	< 10	166
T 26254	201 238	0.02	25	1810	106	5	6	64	0.03	< 10	< 10	83	< 10	190
T 26255	201 238	0.01	27	1480	68	5	2	12	0.01	< 10	< 10	38	< 10	192
T 26256	201 238	0.01	31	960	110	5	7	17	0.02	< 10	< 10	45	< 10	280
T 26257	201 238	0.01	32	810	92	< 5	4	14	0.04	< 10	< 10	50	< 10	190
T 26258	201 238	0.01	27	1020	392	5	6	21	0.03	< 10	< 10	44	< 10	216
T 26259	201 238	0.01	26	1520	166	< 5	4	17	0.03	< 10	< 10	38	< 10	364
T 26260	201 238	0.02	27	1290	190	5	4	16	0.04	< 10	< 10	42	< 10	326
T 26261	201 238	0.01	21	830	318	5	4	13	0.03	< 10	< 10	35	< 10	492
T 26262	201 238	0.01	35	1060	50	5	5	12	0.04	< 10	< 10	49	< 10	300
T 26263	201 238	0.02	24	610	26	5	3	16	0.03	< 10	< 10	33	10	192
T 26264	201 238	0.01	35	1220	52	5	5	12	0.05	< 10	< 10	47	< 10	344
T 26265	201 238	0.01	35	920	68	10	4	13	0.04	< 10	< 10	39	< 10	308
T 26266	201 238	0.02	21	280	38	5	2	17	0.03	< 10	< 10	21	< 10	154
T 26267	201 238	0.01	38	900	74	10	4	13	0.03	< 10	< 10	38	10	270
T 26268	201 238	0.01	17	430	16	10	2	16	0.02	< 10	< 10	23	10	140
T 26269	201 238	0.02	10	140	4	< 5	1	17	0.01	< 10	< 10	12	< 10	70
T 26270	201 238	0.02	16	300	18	5	2	15	0.01	< 10	< 10	18	< 10	92
T 26271	201 238	0.02	21	330	36	10	2	24	0.01	< 10	< 10	18	< 10	158
T 26272	201 238	0.02	41	390	390	10	2	19	0.01	< 10	< 10	20	< 10	600
T 26273	201 238	0.01	42	1640	144	5	3	25	< 0.01	< 10	< 10	12	< 10	468
T 26274	201 238	0.01	45	1380	112	5	3	22	< 0.01	< 10	< 10	11	< 10	486
T 26275	201 238	0.01	46	1590	142	5	4	25	0.01	< 10	< 10	25	< 10	408
T 26276	201 238	0.01	41	1270	58	5	4	25	0.03	< 10	< 10	39	< 10	300
T 26277	201 238	0.01	55	1560	84	< 5	5	26	0.04	< 10	< 10	45	< 10	436
T 26278	201 238	0.01	42	1280	70	5	5	17	0.04	< 10	< 10	48	< 10	320
T 26279	201 238	0.02	25	690	26	5	3	16	0.03	< 10	< 10	31	< 10	144
T 26280	201 238	0.02	29	1180	32	5	4	14	0.04	< 10	< 10	42	< 10	270
T 26281	201 238	0.02	23	750	52	5	3	14	0.02	< 10	< 10	31	< 10	242
T 26282	201 238	0.02	27	720	44	10	3	15	0.02	< 10	< 10	32	< 10	198
T 26283	201 238	0.01	30	1080	72	5	3	16	0.01	< 10	< 10	31	< 10	174
T 26284	201 238	0.01	25	1180	118	< 5	4	15	0.02	< 10	< 10	36	< 10	246
T 26285	201 238	0.01	30	1030	40	< 5	6	16	0.02	< 10	< 10	34	< 10	180
T 26286	201 238	0.01	31	1500	56	5	7	36	0.02	< 10	< 10	45	< 10	134
T 26287	201 238	0.01	20	1360	68	< 5	2	19	0.02	< 10	< 10	49	< 10	146
T 26288	201 238	0.01	26	960	56	< 5	4	16	0.03	< 10	< 10	50	< 10	168
T 26289	201 238	0.01	13	400	32	< 5	2	10	0.06	< 10	< 10	67	< 10	102

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: ?CHER CATHRO & ASSOC. (1981) LTD.

.016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page No : ?-A
Tot. Pa
Date : 28-AUG-89
Invoice # : I-8923493
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26290	201	238	1.85	1.0	< 5	170	< 0.5	< 2	0.38	0.5	16	31	31	4.75	10	< 1	0.08	20	0.55	1480	< 1
T 26291	201	238	1.28	0.8	< 5	210	< 0.5	< 2	0.71	0.5	16	24	70	5.75	10	< 1	0.06	10	0.42	2550	< 1
T 26292	201	238	1.70	0.4	15	370	< 0.5	< 2	0.48	< 0.5	14	31	39	3.86	10	< 1	0.06	10	0.41	1215	< 1
T 26293	201	238	1.21	0.2	20	240	< 0.5	< 2	1.10	< 0.5	15	37	37	4.93	10	1	0.08	10	0.40	2130	< 1
T 26294	201	238	1.68	0.4	5	180	< 0.5	< 2	0.26	< 0.5	16	26	27	4.88	10	< 1	0.05	20	0.39	1620	< 1
T 26295	201	238	1.49	0.6	20	170	< 0.5	< 2	0.29	3.0	67	82	231	10.90	20	< 1	0.07	10	0.72	4970	< 1
T 26296	201	238	1.66	0.2	< 5	260	< 0.5	< 2	0.27	< 0.5	12	26	22	4.74	10	< 1	0.05	20	0.39	1360	< 1
T 26297	201	238	1.79	0.4	< 5	200	< 0.5	< 2	0.28	0.5	7	28	13	3.54	10	< 1	0.05	20	0.45	655	< 1
T 26298	201	238	1.64	0.6	15	200	< 0.5	< 2	0.34	< 0.5	14	24	21	5.01	10	< 1	0.04	20	0.35	1500	< 1
T 26401	201	238	0.80	0.8	55	280	< 0.5	< 2	0.50	< 0.5	16	11	63	4.09	10	< 1	0.06	20	0.28	1445	9
T 26402	201	238	0.74	< 0.2	20	290	< 0.5	< 2	9.51	0.5	16	11	53	5.44	10	1	0.04	< 10	5.56	4740	2
T 26403	201	238	0.36	0.8	< 5	90	< 0.5	< 2	14.25	1.0	12	3	13	3.88	< 10	< 1	0.01	< 10	8.27	4230	< 1
T 26404	201	238	0.76	0.8	< 5	160	< 0.5	< 2	10.80	0.5	15	9	27	5.58	10	< 1	0.03	< 10	6.38	5110	< 1
T 26405	201	238	0.36	0.8	< 5	330	< 0.5	< 2	>15.00	< 0.5	11	2	21	3.44	< 10	< 1	0.01	< 10	8.79	3550	< 1
T 26406	201	238	0.63	0.8	< 5	370	< 0.5	< 2	10.90	0.5	15	10	32	4.73	< 10	< 1	0.03	< 10	6.33	4740	< 1
T 26407	201	238	0.78	0.6	< 5	580	< 0.5	< 2	9.67	0.5	15	9	30	5.31	10	< 1	0.04	< 10	5.73	5360	< 1
T 26408	201	238	0.75	0.8	< 5	510	< 0.5	< 2	9.53	0.5	15	9	40	5.48	10	< 1	0.03	< 10	5.62	5300	< 1
T 26409	201	238	1.22	0.6	15	200	< 0.5	< 2	0.45	< 0.5	17	24	66	4.32	10	< 1	0.11	20	0.42	1305	4
T 26410	201	238	1.20	0.4	< 5	130	< 0.5	< 2	0.23	0.5	15	20	38	4.55	10	< 1	0.09	20	0.34	1200	1
T 26411	201	238	1.27	1.0	15	140	< 0.5	< 2	0.26	< 0.5	17	23	57	4.86	10	< 1	0.08	30	0.48	1125	< 1
T 26412	201	238	1.34	0.6	< 5	170	< 0.5	< 2	0.20	0.5	14	26	70	5.10	10	< 1	0.08	20	0.40	1275	2
T 26413	201	238	1.25	1.6	35	180	0.5	< 2	0.31	< 0.5	18	25	97	6.68	20	< 1	0.09	40	0.63	2450	2
T 26414	201	238	1.71	0.4	10	200	0.5	< 2	0.22	< 0.5	13	29	32	4.99	10	< 1	0.07	20	0.43	1255	1
T 26415	201	238	1.88	0.2	30	130	< 0.5	< 2	0.10	< 0.5	12	30	25	4.78	10	< 1	0.06	10	0.47	1380	1
T 26416	201	238	1.57	0.4	< 5	170	< 0.5	< 2	0.17	1.0	12	30	39	4.14	10	< 1	0.07	10	0.36	1285	< 1
T 26417	201	238	2.25	0.2	< 5	230	< 0.5	< 2	0.28	0.5	13	35	20	3.85	10	< 1	0.07	20	0.50	715	< 1
T 26418	201	238	1.60	0.2	20	150	< 0.5	< 2	0.40	< 0.5	12	32	36	5.05	10	< 1	0.07	20	0.46	1290	1
T 26419	201	238	1.74	0.4	15	230	< 0.5	< 2	0.32	< 0.5	16	32	32	5.03	10	< 1	0.06	20	0.42	1895	< 1
T 26420	201	238	2.26	0.6	30	260	< 0.5	< 2	0.29	< 0.5	14	37	23	3.89	10	< 1	0.06	20	0.68	985	< 1
T 26421	201	238	1.46	1.2	30	270	< 0.5	< 2	0.17	< 0.5	27	30	61	9.21	20	< 1	0.07	30	0.46	5670	< 1
T 26422	201	238	2.22	0.4	25	160	< 0.5	< 2	0.17	< 0.5	13	35	24	3.91	10	< 1	0.07	20	0.56	575	< 1
T 26423	201	238	1.87	0.2	20	180	< 0.5	< 2	0.18	< 0.5	16	30	25	3.75	10	< 1	0.06	20	0.51	995	< 1
T 26424	201	238	2.21	2.2	10	230	< 0.5	< 2	0.14	< 0.5	14	29	15	4.97	10	1	0.05	20	0.38	1695	< 1
T 26425	201	238	1.96	0.6	10	230	< 0.5	< 2	0.33	< 0.5	15	34	23	5.04	10	< 1	0.05	20	0.55	1820	< 1
T 26426	201	238	1.33	0.4	30	120	< 0.5	< 2	0.08	< 0.5	7	20	14	2.96	10	< 1	0.06	20	0.20	715	< 1
T 26427	201	238	1.10	0.2	< 5	180	< 0.5	< 2	0.08	0.5	6	18	8	1.98	10	< 1	0.05	10	0.13	415	< 1
T 26428	201	238	1.95	0.2	35	190	< 0.5	< 2	0.12	< 0.5	9	27	22	3.25	10	< 1	0.07	10	0.46	375	< 1
T 26429	201	238	1.78	0.4	20	110	< 0.5	< 2	0.10	< 0.5	26	29	64	5.01	10	< 1	0.07	10	0.36	1620	2
T 26430	201	238	1.37	0.4	35	100	< 0.5	< 2	0.10	< 0.5	14	27	37	3.68	10	< 1	0.06	10	0.28	595	< 1
T 26431	201	238	1.12	0.4	20	120	< 0.5	< 2	0.05	< 0.5	5	27	23	4.57	10	< 1	0.06	20	0.12	840	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
.016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. :2-B
Tot. P. :4
Date :28-AUG-89
Invoice # :I-8923493
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26290	201	238	0.01	36	890	86	< 5	7	22	0.04	< 10	< 10	52	< 10	134
T 26291	201	238	0.01	23	1660	238	5	7	34	0.02	< 10	< 10	37	< 10	136
T 26292	201	238	0.01	18	1820	74	< 5	5	30	0.02	< 10	< 10	47	< 10	128
T 26293	201	238	0.01	23	1510	72	5	9	44	0.01	< 10	< 10	43	< 10	154
T 26294	201	238	0.01	29	770	74	< 5	6	13	0.02	< 10	< 10	42	< 10	136
T 26295	201	238	0.01	154	630	236	< 5	44	10	< 0.01	< 10	< 10	91	< 10	1260
T 26296	201	238	0.01	24	970	48	< 5	5	13	0.02	< 10	< 10	47	< 10	142
T 26297	201	238	0.01	22	820	34	< 5	2	16	0.03	< 10	< 10	49	< 10	122
T 26298	201	238	0.01	18	1040	58	< 5	5	14	0.02	< 10	< 10	51	< 10	204
T 26401	201	238	0.01	42	1360	54	< 5	3	19	0.01	< 10	< 10	26	< 10	270
T 26402	201	238	0.01	26	700	48	10	3	15	0.01	< 10	< 10	26	10	252
T 26403	201	238	0.02	9	380	28	5	1	13	< 0.01	< 10	< 10	13	10	114
T 26404	201	238	0.02	18	490	52	10	3	16	0.02	< 10	< 10	28	10	160
T 26405	201	238	0.02	10	260	18	5	1	18	< 0.01	< 10	< 10	10	10	90
T 26406	201	238	0.02	17	440	16	5	2	15	0.01	< 10	< 10	18	10	114
T 26407	201	238	0.02	18	560	38	5	2	15	0.02	< 10	< 10	22	10	132
T 26408	201	238	0.02	19	520	62	5	3	16	0.01	< 10	< 10	22	10	170
T 26409	201	238	0.01	39	1050	142	< 5	5	23	0.01	< 10	< 10	31	< 10	268
T 26410	201	238	0.01	25	1000	88	< 5	3	12	0.01	< 10	< 10	34	< 10	172
T 26411	201	238	0.01	38	680	124	5	6	13	0.01	< 10	< 10	36	< 10	320
T 26412	201	238	0.01	36	990	96	< 5	5	12	0.02	< 10	< 10	41	< 10	324
T 26413	201	238	0.01	48	680	156	< 5	10	19	0.03	< 10	< 10	44	< 10	438
T 26414	201	238	0.01	25	1120	66	5	4	13	0.02	< 10	< 10	49	< 10	170
T 26415	201	238	0.01	21	830	52	< 5	3	10	0.03	< 10	< 10	52	< 10	136
T 26416	201	238	0.01	21	1370	46	< 5	2	14	0.02	< 10	< 10	50	< 10	148
T 26417	201	238	0.01	25	910	72	< 5	7	19	0.04	< 10	< 10	59	< 10	138
T 26418	201	238	0.01	26	1040	58	5	5	21	0.03	< 10	< 10	53	< 10	162
T 26419	201	238	0.01	31	960	54	5	7	17	0.03	< 10	< 10	50	< 10	162
T 26420	201	238	0.02	37	720	16	< 5	6	21	0.07	< 10	< 10	57	< 10	114
T 26421	201	238	0.01	38	610	100	10	16	11	0.03	< 10	< 10	52	< 10	266
T 26422	201	238	0.01	28	620	26	< 5	3	15	0.06	< 10	< 10	66	< 10	130
T 26423	201	238	0.01	29	530	34	5	4	13	0.05	< 10	< 10	49	< 10	110
T 26424	201	238	0.01	20	710	38	< 5	3	11	0.04	< 10	< 10	72	< 10	96
T 26425	201	238	0.01	31	880	64	< 5	6	16	0.04	< 10	< 10	54	< 10	128
T 26426	201	238	0.01	11	790	30	< 5	1	9	0.02	< 10	< 10	50	< 10	84
T 26427	201	238	0.01	8	520	8	< 5	1	9	0.04	< 10	< 10	57	< 10	58
T 26428	201	238	0.01	21	780	16	< 5	2	11	0.03	< 10	< 10	47	< 10	118
T 26429	201	238	0.01	32	1340	116	< 5	1	9	0.02	< 10	< 10	55	< 10	120
T 26430	201	238	0.01	20	750	62	5	1	11	0.05	< 10	< 10	60	< 10	104
T 26431	201	238	0.01	19	750	42	5	1	9	0.04	< 10	< 10	74	< 10	100

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No. : 3-A
Tot. Pages : 4
Date : 28-AUG-89
Invoice # : I-8923493
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26432	201	238	2.04	0.2	15	200	< 0.5	2	0.15	< 0.5	12	38	27	4.82	10	< 1	0.07	20	0.50	1435	< 1
T 26433	201	238	1.63	< 0.2	35	210	< 0.5	2	0.28	< 0.5	9	31	22	4.61	10	< 1	0.05	20	0.39	1490	< 1
T 26434	201	238	1.63	< 0.2	35	120	< 0.5	< 2	0.10	< 0.5	14	31	39	4.32	10	< 1	0.06	20	0.50	1775	< 1
T 26435	201	238	1.93	0.6	10	170	< 0.5	4	0.10	< 0.5	12	36	52	4.84	10	< 1	0.09	20	0.51	1245	< 1
T 26436	201	238	2.00	0.2	< 5	240	< 0.5	< 2	0.18	0.5	14	39	41	4.56	10	< 1	0.08	20	0.51	1130	< 1
T 26437	201	238	1.10	12.6	75	1230	< 0.5	2	1.69	< 0.5	31	54	814	13.65	30	< 1	0.07	10	0.81	>10000	< 1
T 26438	201	238	0.97	0.6	55	120	< 0.5	2	0.31	< 0.5	12	16	62	4.32	10	< 1	0.11	40	0.24	1180	2
T 26439	201	238	1.27	2.6	135	280	< 0.5	< 2	0.13	15.0	41	28	301	13.95	30	< 1	0.07	30	0.49	9690	3
T 26440	201	238	1.62	2.2	105	150	< 0.5	< 2	0.14	5.0	34	27	152	11.65	30	< 1	0.08	30	0.67	5640	1
T 26441	201	238	1.60	0.4	< 5	230	< 0.5	< 2	0.26	0.5	12	49	47	4.33	10	< 1	0.07	20	0.40	985	1
T 26442	201	238	1.09	< 0.2	25	130	< 0.5	< 2	0.15	< 0.5	13	22	53	4.47	10	< 1	0.08	30	0.31	865	2
T 26443	201	238	0.68	< 0.2	25	110	< 0.5	< 2	0.17	< 0.5	15	13	73	3.88	10	< 1	0.08	20	0.13	1005	11
T 26444	201	238	0.97	1.0	50	180	< 0.5	< 2	0.96	< 0.5	14	16	84	5.10	20	< 1	0.05	20	0.44	2050	9
T 26445	201	238	0.25	1.0	60	210	< 0.5	< 2	>15.00	< 0.5	15	5	71	4.50	< 10	< 1	0.01	< 10	9.42	4030	< 1
T 26446	201	238	0.07	0.2	20	110	< 0.5	< 2	>15.00	< 0.5	6	1	8	2.08	< 10	< 1	< 0.01	< 10	11.00	2480	< 1
T 26447	201	238	0.57	0.8	45	570	< 0.5	< 2	12.60	< 0.5	12	11	118	5.11	10	< 1	0.03	< 10	7.15	5010	< 1
T 26448	201	238	0.88	1.0	75	630	< 0.5	< 2	8.95	< 0.5	15	16	153	7.05	10	< 1	0.05	< 10	5.10	6450	< 1
T 26449	201	238	1.55	0.8	60	560	< 0.5	< 2	1.78	< 0.5	14	24	99	7.46	20	< 1	0.07	10	0.88	5620	4
T 26450	201	238	0.87	0.6	40	920	< 0.5	< 2	7.23	< 0.5	14	15	45	7.81	20	< 1	0.05	< 10	3.83	8540	1
T 26451	201	238	0.44	0.6	35	720	< 0.5	< 2	12.60	< 0.5	15	10	71	4.58	< 10	< 1	0.04	< 10	7.04	3920	1
T 26452	201	238	0.38	< 0.2	15	1150	< 0.5	< 2	13.70	0.5	14	3	92	5.04	< 10	< 1	0.01	< 10	7.80	4880	3
T 26453	201	238	1.45	0.4	15	560	< 0.5	< 2	3.03	1.0	16	22	113	9.64	20	< 1	0.06	< 10	1.76	7530	1
T 26454	201	238	1.49	1.4	65	620	< 0.5	< 2	1.07	< 0.5	16	23	181	9.31	20	< 1	0.09	20	0.57	6460	4
T 26455	201	238	0.49	1.4	45	90	0.5	< 2	1.05	< 0.5	23	10	113	6.65	10	< 1	0.12	30	0.47	2300	2
T 26456	201	238	0.60	1.8	20	110	< 0.5	< 2	0.79	< 0.5	30	12	116	6.54	10	< 1	0.11	30	0.28	2660	2
T 26457	201	238	1.36	0.6	55	170	0.5	< 2	0.15	< 0.5	22	23	65	5.39	10	< 1	0.11	20	0.50	2840	2
T 26458	201	238	1.39	0.2	20	180	0.5	< 2	0.23	< 0.5	13	28	42	4.42	10	< 1	0.08	20	0.49	1380	1
T 26459	201	238	1.45	0.4	40	110	< 0.5	< 2	0.10	< 0.5	13	32	42	4.61	10	< 1	0.09	20	0.40	925	< 1
T 26460	201	238	1.27	0.4	55	160	0.5	< 2	0.12	< 0.5	18	26	50	4.65	10	< 1	0.11	20	0.44	1875	2
T 26461	201	238	1.21	0.4	45	160	0.5	< 2	0.11	< 0.5	16	25	51	4.75	10	< 1	0.09	20	0.33	1585	< 1
T 26462	201	238	1.35	0.2	< 5	150	< 0.5	< 2	0.11	< 0.5	27	29	55	5.75	20	< 1	0.09	20	0.29	2820	1
T 26463	201	238	0.92	0.8	60	350	< 0.5	< 2	0.83	< 0.5	30	45	93	12.45	30	< 1	0.14	20	0.40	8160	< 1
T 26464	201	238	1.59	3.2	95	180	< 0.5	< 2	0.66	< 0.5	30	21	113	8.73	20	< 1	0.13	40	1.78	4550	7
T 26465	201	238	0.96	1.4	40	80	< 0.5	< 2	0.21	< 0.5	17	12	86	4.48	10	< 1	0.09	40	0.92	990	2
T 26466	201	238	0.98	0.6	30	120	< 0.5	< 2	0.31	< 0.5	11	17	68	5.12	10	< 1	0.07	10	0.26	1205	4
T 26467	201	238	1.65	0.6	10	280	0.5	< 2	0.73	< 0.5	11	29	24	4.85	10	< 1	0.07	20	0.60	1860	< 1
T 26468	201	238	1.54	0.2	30	190	< 0.5	< 2	0.67	< 0.5	13	33	43	4.68	10	< 1	0.08	20	0.68	1240	1
T 26469	201	238	1.72	0.2	< 5	160	0.5	< 2	0.30	< 0.5	14	27	40	4.23	10	< 1	0.08	20	0.66	1500	< 1
T 26470	201	238	1.83	< 0.2	10	110	< 0.5	< 2	0.11	< 0.5	3	29	15	3.15	10	< 1	0.08	20	0.37	315	1
T 26471	201	238	2.08	< 0.2	35	130	0.5	< 2	0.12	< 0.5	14	33	39	4.80	10	< 1	0.10	20	0.61	1130	1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Date :28-AUG-89
Invoice # :I-8923493
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26432	201	238	0.01	31	850	46	< 5	5	13	0.05	< 10	< 10	60	< 10	140
T 26433	201	238	0.01	20	1050	46	< 5	4	15	0.03	< 10	< 10	53	< 10	140
T 26434	201	238	0.01	27	770	38	< 5	5	9	0.04	< 10	< 10	46	< 10	128
T 26435	201	238	0.01	33	610	58	< 5	5	10	0.04	< 10	< 10	53	< 10	146
T 26436	201	238	0.01	27	800	64	< 5	4	14	0.04	< 10	< 10	63	< 10	156
T 26437	201	238	0.01	41	1170	3940	30	20	47	0.02	< 10	< 10	86	20	590
T 26438	201	238	0.01	26	900	78	5	2	16	0.01	< 10	< 10	31	< 10	174
T 26439	201	238	0.01	79	710	514	5	11	10	0.01	< 10	< 10	21	10	5390
T 26440	201	238	0.01	67	910	386	5	6	9	0.01	< 10	< 10	22	< 10	3180
T 26441	201	238	0.01	29	760	114	< 5	6	12	0.02	< 10	< 10	60	< 10	208
T 26442	201	238	0.01	25	620	46	< 5	3	8	0.01	< 10	< 10	36	< 10	154
T 26443	201	238	0.01	49	1310	46	5	1	10	< 0.01	< 10	< 10	25	< 10	136
T 26444	201	238	0.01	43	1290	74	5	5	14	0.02	< 10	< 10	33	< 10	156
T 26445	201	238	0.02	17	210	94	10	1	22	< 0.01	< 10	< 10	13	10	130
T 26446	201	238	0.02	1	80	< 2	5	< 1	18	< 0.01	< 10	< 10	6	10	38
T 26447	201	238	0.02	15	460	40	10	2	16	0.02	< 10	< 10	25	10	220
T 26448	201	238	0.02	27	740	104	5	3	16	0.02	< 10	< 10	34	20	420
T 26449	201	238	0.01	38	1560	60	5	4	16	0.03	< 10	< 10	43	10	372
T 26450	201	238	0.01	27	960	58	10	3	23	0.02	< 10	< 10	34	20	314
T 26451	201	238	0.02	22	360	30	10	2	30	0.01	< 10	< 10	17	20	150
T 26452	201	238	0.02	30	320	38	10	2	28	0.01	< 10	< 10	15	10	232
T 26453	201	238	0.01	44	1240	64	10	4	14	0.03	< 10	< 10	40	10	366
T 26454	201	238	0.01	59	1520	96	15	6	18	0.03	< 10	< 10	44	10	454
T 26455	201	238	0.01	53	690	94	5	8	21	< 0.01	< 10	< 10	14	< 10	300
T 26456	201	238	0.01	47	690	94	< 5	8	21	< 0.01	< 10	< 10	17	< 10	290
T 26457	201	238	0.01	39	1330	84	5	3	7	0.01	< 10	< 10	36	< 10	176
T 26458	201	238	0.01	29	890	66	< 5	3	9	0.02	< 10	< 10	38	< 10	166
T 26459	201	238	0.01	26	640	84	< 5	2	7	0.02	< 10	< 10	47	< 10	140
T 26460	201	238	0.01	29	850	80	< 5	3	8	0.02	< 10	< 10	45	< 10	148
T 26461	201	238	0.01	34	800	64	5	3	9	0.02	< 10	< 10	36	< 10	166
T 26462	201	238	0.01	26	850	118	< 5	5	10	0.03	< 10	< 10	49	< 10	152
T 26463	201	238	0.01	50	820	54	5	21	50	0.01	< 10	< 10	50	10	180
T 26464	201	238	0.01	76	630	156	5	9	29	< 0.01	< 10	< 10	50	10	170
T 26465	201	238	0.01	51	630	44	< 5	6	12	< 0.01	< 10	< 10	36	< 10	78
T 26466	201	238	0.01	35	980	44	< 5	1	14	0.01	< 10	< 10	45	< 10	196
T 26467	201	238	0.01	25	1020	110	5	6	23	0.03	< 10	< 10	48	< 10	220
T 26468	201	238	0.01	29	1170	136	5	8	26	0.02	< 10	< 10	42	< 10	316
T 26469	201	238	0.01	28	680	80	< 5	6	21	0.05	< 10	< 10	44	< 10	162
T 26470	201	238	0.01	18	240	24	< 5	3	12	0.07	< 10	< 10	60	< 10	64
T 26471	201	238	0.01	27	550	48	< 5	4	12	0.05	< 10	< 10	51	< 10	122

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER, BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Date :28-AUG-89
Invoice # :I-8923493
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26472	201	238	1.32	< 0.2	20	190	< 0.5	< 2	1.30	1.0	10	22	51	3.01	10	< 1	0.07	10	0.58	1025	< 1
T 26473	201	238	1.04	0.2	25	180	< 0.5	< 2	0.21	< 0.5	10	27	32	4.14	10	< 1	0.08	10	0.25	1185	1
T 26474	201	238	0.57	0.8	20	60	< 0.5	< 2	0.07	< 0.5	8	11	63	3.82	10	< 1	0.08	20	0.16	500	3
T 26475	201	238	1.02	0.4	20	110	< 0.5	< 2	0.11	< 0.5	13	24	120	7.74	20	< 1	0.10	30	0.33	2230	2
T 26476	201	238	1.15	1.4	60	50	< 0.5	< 2	0.25	< 0.5	15	17	107	4.43	10	< 1	0.18	40	0.94	615	2
T 26477	201	238	0.63	1.6	110	110	< 0.5	< 2	0.67	< 0.5	31	11	174	7.84	20	< 1	0.11	40	0.55	2220	6
T 26478	201	238	0.37	1.2	45	90	< 0.5	< 2	2.84	< 0.5	31	9	97	4.15	10	< 1	0.13	< 10	1.18	1410	4
T 26479	201	238	0.88	0.4	65	320	< 0.5	< 2	0.57	< 0.5	26	22	36	6.27	20	< 1	0.11	20	0.22	5670	1
T 26480	201	238	1.20	0.2	45	180	< 0.5	< 2	0.32	< 0.5	14	24	33	5.41	10	< 1	0.11	20	0.43	2270	2
T 26481	201	238	1.04	< 0.2	35	230	< 0.5	< 2	0.09	< 0.5	15	22	34	4.73	10	< 1	0.09	20	0.32	3350	< 1
T 26482	201	238	0.83	1.4	75	90	0.5	< 2	0.74	0.5	17	20	90	6.13	10	< 1	0.09	40	0.40	1975	1
T 26483	201	238	0.90	0.8	45	170	< 0.5	< 2	1.77	< 0.5	15	17	54	4.99	10	< 1	0.13	20	0.83	2320	1
T 26484	201	238	0.94	0.2	< 5	160	< 0.5	< 2	0.16	0.5	15	23	42	4.43	10	< 1	0.14	20	0.27	2220	2
T 26485	201	238	0.99	1.8	< 5	100	0.5	< 2	0.22	0.5	11	20	42	3.91	10	< 1	0.09	30	0.36	855	1
T 26486	201	238	0.80	0.8	65	120	< 0.5	< 2	0.18	< 0.5	15	15	54	5.91	10	< 1	0.15	40	0.22	2360	4
T 26487	201	238	0.77	1.6	35	80	0.5	< 2	0.54	< 0.5	13	16	45	4.92	10	< 1	0.14	40	0.28	1355	4
T 26488	201	238	0.11	< 0.2	< 5	180	< 0.5	< 2	>15.00	0.5	6	< 1	13	3.53	< 10	< 1	< 0.01	< 10	9.59	4010	< 1
T 26489	201	238	0.59	0.8	60	280	< 0.5	< 2	5.26	< 0.5	18	11	77	6.77	10	< 1	0.06	< 10	2.99	3830	9
T 26490	201	238	0.42	0.4	35	180	< 0.5	< 2	11.85	< 0.5	9	9	41	3.91	< 10	< 1	0.02	< 10	6.78	3500	2
T 26491	201	238	0.25	0.4	15	1150	< 0.5	< 2	>15.00	< 0.5	11	7	60	3.50	< 10	< 1	0.01	< 10	8.65	3040	< 1
T 26492	201	238	1.30	0.2	40	260	< 0.5	< 2	7.07	< 0.5	13	28	56	6.94	20	< 1	0.06	< 10	4.16	5910	5

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To CHER CATHRO & ASSOC. (1981) LTD.
...016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page No -B
Tot. Pa
Date :28-AUG-89
Invoice # :I-8923493
P.O. # :NONE

CERTIFICATE OF ANALYSIS A8923493

SAMPLE DESCRIPTION	PREP CODE	Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26472	201 238	0.01	17	1090	30	5	2	62	0.02	< 10	< 10	35	< 10	354
T 26473	201 238	0.01	21	1030	56	< 5	1	12	0.01	< 10	< 10	50	< 10	150
T 26474	201 238	0.01	34	740	22	5	1	5	< 0.01	< 10	< 10	31	< 10	194
T 26475	201 238	0.01	37	1480	60	5	3	7	0.01	< 10	< 10	55	< 10	154
T 26476	201 238	0.01	54	630	46	5	7	9	< 0.01	< 10	< 10	16	< 10	86
T 26477	201 238	0.01	67	670	100	5	8	14	< 0.01	< 10	< 10	35	10	116
T 26478	201 238	0.01	55	580	94	10	5	74	< 0.01	< 10	< 10	20	10	248
T 26479	201 238	0.01	34	1400	84	5	2	23	0.01	< 10	< 10	41	10	194
T 26480	201 238	0.01	30	830	64	5	3	10	0.02	< 10	< 10	43	10	178
T 26481	201 238	0.01	26	1210	60	< 5	1	6	0.01	< 10	< 10	42	< 10	150
T 26482	201 238	0.01	60	1000	52	< 5	10	13	< 0.01	< 10	< 10	19	< 10	428
T 26483	201 238	0.01	50	1140	46	< 5	7	19	0.01	< 10	< 10	27	10	284
T 26484	201 238	0.01	32	1160	52	< 5	2	7	0.01	< 10	< 10	34	< 10	148
T 26485	201 238	0.01	41	550	38	5	7	10	0.02	< 10	< 10	28	< 10	196
T 26486	201 238	0.01	52	1050	70	5	9	6	0.01	< 10	< 10	24	< 10	506
T 26487	201 238	0.01	49	1050	40	5	8	9	< 0.01	< 10	< 10	23	< 10	394
T 26488	201 238	0.02	9	110	< 2	5	1	26	< 0.01	< 10	< 10	5	10	62
T 26489	201 238	0.01	63	950	48	10	5	20	0.01	< 10	< 10	18	20	252
T 26490	201 238	0.02	16	270	24	10	2	20	0.01	< 10	< 10	16	10	118
T 26491	201 238	0.02	12	140	6	10	1	33	< 0.01	< 10	< 10	12	10	96
T 26492	201 238	0.02	41	760	32	5	5	22	0.03	< 10	< 10	43	20	244

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

T ARCHER CATHRO & ASSOC. (1981) LTD.

1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8

Project : BLENDE
Comments:

Page : 1
Tot. Pages: 1
Date : 11-OCT-89
Invoice # : I-8924642
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8924642

SAMPLE DESCRIPTION	PREP CODE		Ag oz/T	Cu %	Pb %	Zn %	Ge %
T 21995	208	--	0.56	0.02	1.06	14.80	-----
T 21996	208	--	2.68	0.01	12.90	12.30	-----
T 21997	208	--	0.11	< 0.01	0.25	2.09	-----
T 24499	208	--	2.30	< 0.01	5.20	6.48	-----
T 24500	208	--	3.68	< 0.01	8.20	1.86	-----
T 24501	208	--	7.37	< 0.01	11.70	4.60	-----
T 24502	208	--	3.79	< 0.01	4.40	8.69	-----
T 24503	208	--	6.56	0.03	7.50	6.72	-----
T 24689	208	--	30.3	2.97	8.67	1.92	0.003
T 24876	208	--	6.71	10.50	0.14	0.07	-----
T 24877	208	--	0.33	0.14	0.15	0.08	-----
T 24878	208	--	0.91	0.06	0.15	0.92	-----

CERTIFICATION : Hart Bichler

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 11-SEP-89
Invoice # : I-8924643
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8924643

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 21419	217	238	2.72	0.2	70	120	< 0.5	< 2	0.81	< 0.5	24	74	104	6.47	20	< 1	0.16	10	3.21	4700	1
T 21420	201	238	1.05	0.2	15	70	< 0.5	4	1.98	< 0.5	23	12	55	5.80	10	1	0.12	20	1.29	3110	< 1
T 21421	201	238	0.59	0.2	30	70	< 0.5	6	2.58	< 0.5	17	5	44	5.78	10	< 1	0.16	10	1.46	5120	< 1
T 21422	203	238	0.97	< 0.2	55	100	< 0.5	4	3.24	< 0.5	17	39	48	3.91	10	< 1	0.31	10	2.07	3090	< 1
T 21423	201	238	0.62	0.2	5	80	< 0.5	4	3.60	< 0.5	16	8	56	4.30	10	< 1	0.14	10	1.99	3610	< 1
T 21424	201	238	0.58	0.6	45	130	< 0.5	< 2	0.61	< 0.5	30	4	56	4.85	10	< 1	0.16	30	0.42	4740	1
T 21428	201	238	1.52	0.6	35	120	< 0.5	4	1.47	< 0.5	16	18	42	5.20	10	< 1	0.31	20	1.67	3290	< 1
T 21429	201	238	1.43	0.8	25	120	< 0.5	4	1.22	< 0.5	16	19	40	4.97	10	< 1	0.30	20	1.55	3240	< 1
T 21430	201	238	0.87	0.6	10	50	< 0.5	2	0.94	0.5	11	13	40	4.66	10	< 1	0.20	30	0.69	1030	< 1
T 21431	201	238	0.54	0.6	25	80	< 0.5	< 2	1.05	< 0.5	12	8	33	5.70	10	< 1	0.09	20	0.49	3310	< 1
T 21432	203	238	0.56	0.6	20	70	< 0.5	4	1.31	0.5	14	43	38	4.01	10	< 1	0.19	20	0.64	2480	< 1
T 21433	201	238	0.42	0.4	25	70	< 0.5	< 2	1.62	< 0.5	17	2	64	6.08	10	< 1	0.08	10	0.71	4560	1
T 21981	201	238	0.17	24.6	120	10	< 0.5	< 2	7.93	28.5	40	1	128	4.53	< 10	3	0.03	< 10	4.65	1695	< 1
T 21982	201	238	0.33	5.4	90	40	< 0.5	< 2	10.20	6.5	23	5	340	6.72	< 10	2	0.04	< 10	6.05	1885	< 1
T 21983	201	238	0.52	4.0	135	40	< 0.5	< 2	6.98	17.0	38	8	328	10.05	< 10	13	0.08	< 10	4.23	1570	< 1
T 21984	201	238	0.17	25.8	70	< 10	< 0.5	< 2	9.53	39.0	26	3	138	2.61	< 10	2	0.07	< 10	5.62	1030	< 1
T 21990	201	238	0.25	81.8	220	< 10	< 0.5	14	7.20	64.5	66	7	414	6.34	< 10	9	0.06	< 10	4.19	2250	3
T 21991	201	238	0.41	23.4	190	70	< 0.5	26	2.36	25.0	132	9	121	5.47	10	1	0.07	< 10	1.37	2540	1
T 21992	201	238	0.27	58.6	115	10	< 0.5	< 2	8.95	63.5	35	4	268	3.52	< 10	6	0.04	< 10	5.27	2150	< 1
T 21993	201	238	0.78	36.4	90	30	< 0.5	22	3.66	11.5	71	10	385	4.01	< 10	4	0.09	< 10	2.28	1940	1
T 21994	201	238	0.41	68.0	175	20	< 0.5	< 2	9.07	22.5	57	8	587	4.25	< 10	5	0.04	< 10	5.33	2050	< 1
T 24633	201	238	0.56	4.0	20	30	1.0	12	3.97	1.0	18	11	10	2.26	< 10	1	0.28	< 10	2.42	515	< 1
T 24637	201	238	0.44	1.6	50	50	1.0	18	3.29	3.0	33	10	39	3.53	< 10	1	0.09	10	1.88	1140	< 1
T 24638	201	238	0.53	< 0.2	15	100	< 0.5	< 2	8.44	5.0	12	11	44	3.20	< 10	2	0.04	< 10	4.90	3570	< 1
T 24639	201	238	0.37	< 0.2	5	40	< 0.5	< 2	8.02	6.0	18	7	44	2.18	< 10	1	0.04	< 10	4.50	1765	< 1
T 24640	201	238	0.36	< 0.2	15	50	< 0.5	< 2	8.90	13.0	15	10	54	4.14	< 10	< 1	0.05	< 10	5.07	4600	< 1
T 24642	201	238	0.33	< 0.2	5	40	< 0.5	< 2	9.39	3.5	8	6	36	2.79	< 10	< 1	0.02	< 10	5.37	2410	< 1
T 24643	201	238	0.52	0.4	20	60	< 0.5	< 2	5.90	2.5	12	12	64	3.83	< 10	< 1	0.08	< 10	3.34	2880	< 1
T 24644	201	238	0.42	0.8	5	90	< 0.5	8	2.13	1.0	11	7	58	3.46	10	< 1	0.10	20	1.14	3250	< 1
T 26135	201	238	0.54	1.8	75	70	< 0.5	6	1.17	0.5	65	8	97	5.89	10	< 1	0.09	20	0.64	1710	1
T 26136	201	238	0.54	< 0.2	55	100	< 0.5	< 2	7.48	1.0	48	11	54	5.65	< 10	< 1	0.07	< 10	4.18	3660	< 1
T 26137	201	238	0.15	4.6	115	10	< 0.5	< 2	8.68	16.5	40	4	70	4.13	< 10	1	0.03	< 10	4.94	1850	< 1
T 26138	201	238	0.27	5.2	65	30	< 0.5	< 2	8.56	10.5	24	2	1245	4.73	< 10	1	0.02	< 10	4.80	2060	1
T 26139	201	238	0.32	< 0.2	65	50	< 0.5	< 2	7.95	3.5	20	8	53	4.50	< 10	< 1	0.04	< 10	4.48	2080	< 1
T 26140	201	238	1.09	1.6	55	200	< 0.5	< 2	0.40	< 0.5	32	18	62	6.69	10	< 1	0.12	30	0.45	1595	< 1
T 26141	201	238	0.68	32.8	65	50	< 0.5	8	3.06	6.5	28	11	209	4.90	< 10	1	0.06	< 10	1.77	1890	1
T 26142	201	238	0.32	19.8	50	10	< 0.5	< 2	10.30	22.0	16	7	163	4.24	< 10	1	0.03	< 10	6.02	2110	< 1
T 26143	201	238	0.19	1.0	75	30	< 0.5	< 2	10.75	4.0	19	< 1	187	4.54	< 10	< 1	0.05	< 10	6.16	1580	< 1
T 26144	201	238	0.15	< 0.2	< 5	20	< 0.5	< 2	10.35	4.5	5	4	39	1.78	< 10	< 1	0.01	< 10	6.04	1245	< 1
T 26145	201	238	0.31	< 0.2	30	60	< 0.5	< 2	9.57	2.0	18	6	97	3.49	< 10	< 1	0.05	< 10	5.55	2050	< 1

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.
3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9
Project : BLENDE
Comments:

Date : 11-SEP-89
Invoice # : I-8924643
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8924643

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 21419	217	238	0.01	30	800	50	10	11	10	0.01	< 10	< 10	61	< 10	284
T 21420	201	238	0.01	23	1150	24	5	10	18	0.01	< 10	< 10	42	< 10	142
T 21421	201	238	0.01	23	950	10	5	8	27	0.01	< 10	< 10	13	< 10	76
T 21422	203	238	0.01	19	920	58	10	6	21	0.02	< 10	< 10	32	< 10	104
T 21423	201	238	0.01	18	900	24	5	6	28	0.02	< 10	< 10	22	< 10	114
T 21424	201	238	0.01	31	780	44	5	5	11	0.01	< 10	< 10	17	< 10	138
T 21428	201	238	0.01	24	930	34	10	7	20	0.02	< 10	< 10	34	< 10	452
T 21429	201	238	0.01	24	880	34	10	7	17	0.02	10	< 10	32	< 10	434
T 21430	201	238	0.01	21	1060	44	5	6	14	0.01	< 10	< 10	21	< 10	242
T 21431	201	238	0.01	18	950	34	5	5	15	< 0.01	10	< 10	15	< 10	244
T 21432	203	238	0.01	16	760	28	10	4	17	0.01	< 10	< 10	14	< 10	232
T 21433	201	238	0.01	22	910	28	10	5	21	< 0.01	< 10	< 10	14	< 10	120
T 21981	201	238	0.01	42	350	>10000	50	4	23	< 0.01	10	< 10	7	10	>10000
T 21982	201	238	0.02	35	230	1580	55	4	27	< 0.01	10	< 10	14	< 10	5060
T 21983	201	238	0.02	49	370	948	40	6	17	0.01	10	10	17	10	>10000
T 21984	201	238	0.01	28	320	>10000	60	3	32	< 0.01	10	< 10	7	20	>10000
T 21990	201	238	0.02	64	600	>10000	110	4	49	< 0.01	< 10	10	10	40	>10000
T 21991	201	238	0.01	113	670	>10000	40	5	18	0.01	< 10	10	13	20	>10000
T 21992	201	238	0.01	32	520	>10000	75	3	39	< 0.01	< 10	< 10	11	40	>10000
T 21993	201	238	0.01	62	710	>10000	200	5	18	0.02	< 10	< 10	24	30	>10000
T 21994	201	238	0.02	43	420	>10000	190	4	35	0.01	< 10	< 10	15	30	>10000
T 24633	201	238	0.01	30	610	1650	15	8	20	0.01	< 10	< 10	13	< 10	1450
T 24637	201	238	0.01	38	700	1090	20	6	19	0.02	< 10	< 10	18	< 10	1510
T 24638	201	238	0.02	16	550	170	15	4	16	0.01	< 10	< 10	20	< 10	3630
T 24639	201	238	0.01	19	550	636	10	4	43	0.01	< 10	< 10	15	10	4510
T 24640	201	238	0.02	17	530	916	10	5	28	< 0.01	10	< 10	15	10	6230
T 24642	201	238	0.02	11	430	284	10	4	25	0.01	< 10	< 10	15	< 10	2450
T 24643	201	238	0.02	17	680	232	10	6	28	0.01	< 10	< 10	18	< 10	2310
T 24644	201	238	0.01	16	650	104	5	5	16	< 0.01	10	< 10	12	< 10	144
T 26135	201	238	0.01	65	520	324	30	6	8	0.01	10	< 10	15	< 10	626
T 26136	201	238	0.02	73	660	138	25	5	34	0.01	10	< 10	21	< 10	856
T 26137	201	238	0.01	48	360	2990	30	4	27	< 0.01	< 10	< 10	7	10	>10000
T 26138	201	238	0.01	32	390	854	90	5	26	< 0.01	< 10	< 10	12	< 10	6050
T 26139	201	238	0.02	31	490	148	25	4	22	< 0.01	< 10	< 10	12	< 10	1790
T 26140	201	238	0.01	46	800	140	15	9	13	0.03	< 10	< 10	34	< 10	594
T 26141	201	238	0.01	43	850	7940	100	6	39	0.01	< 10	< 10	26	< 10	7010
T 26142	201	238	0.02	23	410	>10000	60	4	51	0.01	< 10	< 10	14	< 10	>10000
T 26143	201	238	0.02	31	190	1545	30	4	49	< 0.01	< 10	< 10	8	< 10	2510
T 26144	201	238	0.02	13	130	270	5	2	24	< 0.01	< 10	< 10	7	< 10	1405
T 26145	201	238	0.02	26	320	328	10	5	34	< 0.01	< 10	< 10	12	< 10	1170

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 2-A
Tot. Pages: 2
Date : 11-SEP-89
Invoice # : I-8924643
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8924643

SAMPLE DESCRIPTION	PREP CODE		Al %	Ag ppm	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	Hg ppm	K %	La ppm	Mg %	Mn ppm	Mo ppm
T 26361	201	238	0.37	9.6	85	170	< 0.5	< 2	8.24	10.5	19	4	169	4.75	< 10	< 1	0.03	< 10	4.77	2140	< 1
T 26362	203	238	0.67	12.2	65	640	< 0.5	< 2	6.75	16.5	31	45	203	3.62	< 10	2	0.21	< 10	4.11	1555	< 1
T 26363	201	238	0.19	28.2	50	40	< 0.5	< 2	9.56	25.5	19	4	113	3.15	< 10	2	0.05	< 10	5.60	1655	< 1
T 26364	203	238	0.25	< 0.2	10	30	< 0.5	< 2	10.55	1.5	12	28	49	2.65	< 10	< 1	0.13	< 10	6.18	1210	< 1
T 26365	201	238	0.39	3.0	60	50	< 0.5	< 2	4.51	1.5	40	4	393	3.85	< 10	< 1	0.12	< 10	2.53	2190	2
T 26366	201	238	0.43	1.4	55	70	< 0.5	2	3.46	< 0.5	33	4	201	3.82	< 10	< 1	0.14	10	1.88	2290	2
T 26367	201	238	0.50	4.4	55	80	< 0.5	4	2.12	< 0.5	36	7	155	4.90	10	< 1	0.13	20	1.20	3280	1
T 26400	201	238	0.85	2.4	50	190	< 0.5	< 2	0.71	< 0.5	71	11	868	6.66	10	1	0.10	30	0.34	3090	2

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDF
Comments:

Date : 11-SEP-89
Invoice # : I-8924643
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8924643

SAMPLE DESCRIPTION	PREP CODE		Na %	Ni ppm	P ppm	Pb ppm	Sb ppm	Sc ppm	Sr ppm	Ti %	Tl ppm	U ppm	V ppm	W ppm	Zn ppm
T 26361	201	238	0.01	37	470	6880	30	4	56	0.01	< 10	< 10	14	< 10	7320
T 26362	203	238	0.01	40	470	6050	35	8	38	< 0.01	< 10	< 10	35	< 10	>10000
T 26363	201	238	0.01	23	300	>10000	40	4	44	< 0.01	< 10	< 10	11	10	>10000
T 26364	203	238	0.02	17	200	1090	10	3	46	< 0.01	10	< 10	8	< 10	942
T 26365	201	238	0.01	33	810	204	20	5	70	< 0.01	< 10	< 10	12	< 10	1420
T 26366	201	238	0.01	26	1030	70	15	5	86	< 0.01	< 10	< 10	11	< 10	244
T 26367	201	238	0.01	25	800	74	20	7	50	0.01	< 10	< 10	14	< 10	186
T 26400	201	238	0.01	48	780	600	15	9	12	0.01	< 10	< 10	24	< 10	730

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

To: ARCHER CATHRO & ASSOC. (1981) LTD.
316 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments:

Page No : 1
Tot. Pa
Date : 05-OCT-89
Invoice # : I-8925876
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8925876

SAMPLE DESCRIPTION	PREP CODE		In NAA ppm	Ge %
H 53380	214	--	3	0.001
K 7772	214	--	-----	0.001
SO9993-96	214	--	10	-----
T 24503	214	--	10	-----

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 1
Tot. Pages: 3
Date : 19-SEP-89
Invoice # : I-8925877
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8925877

SAMPLE DESCRIPTION	PREP CODE		Au ppb FA+AA
T 23240	214	--	< 5
T 23783	214	--	< 5
T 23784	214	--	< 5
T 23785	214	--	< 5
T 23786	214	--	< 5
T 23787	214	--	< 5
T 23788	214	--	< 5
T 23789	214	--	< 5
T 23790	214	--	< 5
T 23791	214	--	5
T 23696	214	--	< 5
T 23792	214	--	< 5
T 23793	214	--	15
T 23794	214	--	< 5
T 23795	214	--	5
T 23796	214	--	10
T 23797	214	--	5
T 23798	214	--	< 5
T 23800	214	--	< 5
T 23801	214	--	< 5
T 24026	214	--	< 5
T 24027	214	--	< 5
T 24028	214	--	< 5
T 23879	214	--	< 5
T 24370	214	--	< 5
T 24371	214	--	5
T 24372	214	--	< 5
T 24373	214	--	< 5
T 24374	214	--	< 5
T 24375	214	--	< 5
T 24376	214	--	< 5
T 24377	214	--	< 5
T 24378	214	--	5
T 24379	214	--	5
T 24380	214	--	5
T 24381	214	--	< 5
T 24418	214	--	< 5
T 24419	214	--	5
T 24420	214	--	< 5
T 24421	214	--	< 5

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists * Geochemists * Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Date : 19-SEP-89
Invoice # : I-8925877
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8925877

SAMPLE DESCRIPTION	PREP CODE		Au ppb FA+AA
T 24422	214	--	< 5
T 24423	214	--	< 5
T 24424	214	--	5
T 24425	214	--	< 5
T 24426	214	--	< 5
T 24427	214	--	5
T 24428	214	--	< 5
T 24429	214	--	< 5
T 24430	214	--	< 5
T 24431	214	--	5
T 24432	214	--	< 5
T 24433	214	--	< 5
T 24434	214	--	5
T 24435	214	--	< 5
T 24562	214	--	< 5
T 24966	214	--	10
T 24697	214	--	< 5
T 24698	214	--	< 5
T 24699	214	--	< 5
T 24700	214	--	< 5
T 24701	214	--	< 5
T 24702	214	--	< 5
T 24747	214	--	5
T 24748	214	--	< 5
T 24749	214	--	< 5
T 24750	214	--	< 5
T 24794	214	--	< 5
T 24795	214	--	< 5
T 24796	214	--	< 5
T 25030	214	--	< 5
T 25140	214	--	< 5
T 25141	214	--	< 5
T 25142	214	--	15
T 25143	214	--	10
T 25144	214	--	< 5
T 25145	214	--	< 5
T 25146	214	--	< 5
T 25147	214	--	< 5
T 25148	214	--	5
T 25149	214	--	< 5

CERTIFICATION : _____

Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

ARCHER CATHRO & ASSOC. (1981) LTD.

3125 3RD AVE., BOX 4127
WHITEHORSE, YT
Y1A 3S9

Project : BLENDE
Comments:

Page : 3
Tot. Pages: 3
Date : 19-SEP-89
Invoice # : I-8925877
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8925877

SAMPLE DESCRIPTION	PREP CODE		Au ppb FA+AA
T 25224	214	--	5
T 25225	214	--	< 5
T 25226	214	--	< 5
T 25477	214	--	< 5
T 25532	214	--	< 5
T 25552	214	--	< 5
T 25553	214	--	15
T 25559	214	--	< 5
T 25600	214	--	< 5
T 25622	214	--	10
T 25953	214	--	< 5
T 25340	214	--	< 5
T 25691	214	--	< 5
T 25758	214	--	< 5
T 25816	214	--	< 5
T 25903	214	--	< 5
T 26220	214	--	< 5
T 26265	214	--	5
T 26480	214	--	< 5

CERTIFICATION : _____

Chemex Labs Ltd.
Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1
PHONE (604) 984-0221

T 'RCHER CATHRO & ASSOC. (1981) LTD.
1016 - 510 W. HASTINGS ST.
VANCOUVER, BC
V6B 1L8
Project : BLENDE
Comments: ATTN: DIANE LISTER

Page N° : 1
Tot. : 1
Date : 28-NOV-89
Invoice # : I-8929482
P.O. # : NONE

CERTIFICATE OF ANALYSIS A8929482

SAMPLE DESCRIPTION	PREP CODE		In NAA ppm	Ge %
K 7772	214	--	15	-----
T 24503	214	--	-----	0.002
T 24689	214	--	152	-----

CERTIFICATION : Arnold O. Byers



APPENDIX D

1988 DRILL LOGS

092795

PROJECT NDU-BLENDE | TARGET 5 & 7 ZONES | CORE SIZE NQ 0-222.59 | HOLE NUMBER 88-B-1

COORDINATES 20 003.32N, 10279.37E | AZIMUTH 032.5° | ELEVATION 1796.16 m | PAGE 1 OF 15

HOLE ANGLE -50° | FINAL DEPTH 222.59 | DATE STARTED JULY 6 1988 | DATE FINISHED JULY 12 1988

LOGGED BY M P PHILLIPS

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION: QZ MODE / AMT	SD MODE / AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE / AMT	SL MODE / AMT	HZ MODE / AMT	PY MODE / AMT	LI MODE / AMT	SAMPLING DETAILS & ASSAY RESULTS: SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
0	CASING: NONE. CORING.																	
4.27	HIGHLY OXIDIZED; OXIDIZED SD-SX VLTS <5cm. GL PARTLY OXIDIZED; PY±SL TO LI. DOLOMITE				50							4.27						
5.20	OXIDIZED 1-2cm SD-SX VLTS TRACES GL				10							5.79						
6.20	SD VLTS WITH SD-SX VLTS	0	<1	1	60	5	<1	<1	C%	0	<F	59971	80	1.52	<0.002	4.49	11.20	5.96
7.03	HEAVY LI	0	0				0	0	0	0	P.F	59972	80	1.53	<0.002	2.57	4.89	3.04
7.55	HIGHLY FRACTURED; WIDELY SPACED <5cm LI (SD+SX) VLTS	0	<1		50		0	0	0	0	<F	59973	80	1.52	<0.002	1.78	4.53	4.34
												7.32						
												59974	85	1.52	<0.002	0.34	1.21	4.13
												8.84						
11.15	12cm BRECCIATED SD VEIN, STRONG OXD - MINOR GL											59975	85	1.83	<0.002	0.20	0.54	1.67
												10.36						
12.28	FRACTURED, WEAK BRECCIATED OXD. SD VLTS; LI IN <1cm BANDS	0	<2		10	1-2	B1	0	<1	0	<M	59976	85	1.53	<0.002	1.12	3.11	4.69
13.15												12.19						
13.36	WEAK SD+LI VLTS, TRACE GL	0	<1			<2	B%	0	C<	0	VF	59977	90	1.52	<0.002	0.42	1.17	0.85
												13.72						
15																		

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 2 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
15																													
	0		<>				<2	B*		0		CC		0		VF													
17.07																													
	0		<>			10	2	<>		0		CC		0		<F													
21.34																													
21.75																													
	0		<+			5		D>		0		C+		0		<F													
22.85																													
24.0																													
	0		<1			10		D+		0		C+		0		<M													
24.75																													
	0		<>			3	1-2	D*		0		0		0		L													
26.57																													
27.75																													
	0		<1					D>		0		C+		0		PH													
28.48																													
	0		<>			3	1-2	D+		0		0		0		L													
30																													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
15.24						
S9978	90	1.83	<0.002	0.48	1.19	2.29
17.07						
S8360	100	1.52	<0.002	0.09	0.20	0.18
18.59						
S8361	100	1.53	<0.002	0.47	1.08	0.51
20.12						
S8362	100	1.22	<0.002	0.22	0.58	0.52
21.34						
S9979	90	1.82	<0.002	1.33	3.48	4.25
23.16						
S9980	90	1.83	<0.002	1.28	3.18	3.14
24.99						
S8363	100	1.53	<0.002	0.15	0.40	0.67
26.52						
S8364	100	0.91	<0.002	0.36	0.91	1.10
27.43						
S9981	90	1.53	<0.002	6.17	17.10	13.70
28.96						
S8365	100	1.52	<0.002	0.31	0.82	0.52

15 — DOLOMITE

17.07 — SD VLTS - WEAK MINOR GL, WEAK HZ, WEAK OXD.

21.34 — HIGHLY OXD. MODERATE LI, MINOR GL, WEAK HZ

21.75 — INCREASED SD STRONG LI, FAIR GL

22.85

24.0 — <20 CM BANDS, <1cm SD VLTS-STRONG LI

24.75

26.57 — 1cm SD-GL-HZ VLT

27.75 — HEAVY OXD. BRECCIA? HEAVY LI FAIR <3cm GL MINOR CE+HZ

28.48

30

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 3 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
30																													
DOLOMITE	0	<>				3	1-2	D/A	*	0		0		0		L													
33.10 12cm SD VLTS WEAK & MINOR HZ																													
34.45 INCREASED SD VLTS WITH SX	<D	*	<1			10	5	<>	D	0		<>		0		<F													
34.55 15cm STRONG LT-BRECCIA																													
SD VLTS TO 3cm WITH GL±HZ	8	+	<2					<>		0		<+		0		<+													
37.15 MODERATE SD VLT WITH GL & MINOR FRACTURE SX	<-		<1		3	30	5	<+		<>		0		0		VL													
38.55 22 cm SD VEIN - MINOR QZ, FINE BLEBS GL, TRACE HZ																													
42.98 WEAK SX SD	0	<1				10	2-3	<+	*	0		0		0		<M													
43.68 12cm SD-QZ VEIN - COARSE BLEB GL																													
SD VLT WEAKEN - MINOR SX	0	<=				25		<=	D/C	0		0		0		VL													
45																													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
30.48						
S8366	100	1.52	<0.002	0.04	0.07	0.27
32.00						
S8367	95	1.53	<0.002	0.09	0.25	0.43
33.53						
S8368	95	1.52	<0.002	0.36	0.98	0.32
35.05						
S8369	90	1.53	<0.002	0.22	0.48	1.59
36.58						
S8370	100	1.52	<0.002	0.70	1.38	2.13
38.10						
S8982	90	1.52	<0.002	0.76	1.80	1.11
39.62						
S8371	100	2.14	<0.002	0.34	0.89	0.65
41.76						
S8372	100	1.22	0.002	0.47	0.98	1.17
42.98						
S8983	90	0.51	<0.002	3.67	7.17	4.24
43.89						
S8373	100	0.92	<0.002	0.16	0.37	0.55
44.81						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 4 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI															
MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
45						
DOLOMITE						
0	<=		25	_	<<C	<<C	0	0	<L																					
46.5																														
WEAK SD VLTS WITH TRACE WEAK GL SL PY HZ																														
0	<>	1	15	2	<>	<C	C*	<*	VL																					
S8374 S8375	100	3.04	<0.002	0.29	0.63	0.74																								
47.85																														
S8376	100	1.53	<0.002	0.17	0.38	0.48																								
49.38																														
S8377	100	1.52	<0.002	0.05	0.11	0.14																								
50.90																														
S8378	100	1.53	<0.002	0.06	0.11	0.09																								
52.43																														
S8379	100	1.52	<0.002	0.13	0.30	0.18																								
54.05																														
53.95																														
-15-40cm BANDS SD VLTS WITH INCREASED GL, SL, PY, SD ...VLTS OFTEN OXD..																														
	<>		30	10	<+	0	C*	D	<F																					
S8380	100	1.52	<0.002	0.60	1.68	0.89																								
55.47																														
S8381	100	1.53	<0.002	0.05	0.32	0.25																								
57.0																														
57.00																														
S8382	100	1.52	<0.002	0.09	0.20	0.11																								
58.52																														
S8383	100	1.83	<0.002	0.13	0.37	0.05																								
60																														
0	1	15	2	<>	<C	C*	<*	VL																						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 5 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
60.45 DOLOMITE	0	<>	1		15	2	<>	<<		C#		K#		VF															
SLIGHT INCREASE IN SX IN. 2-5mm SD VLTS VARIABLE OXD																													
63.40																													
71.02																													
STRONG GL, HZ, PY & LI IN SD VLTS	0	<1	3		10	3	<=	0	<>	DK		VM																	
71.57	0	<>	1		15	2	<>	<<		C#		K#		VF															
75																													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
60.35						
S8384	90	3.05	0.002	0.35	0.51	0.55
63.40						
S8384	100	1.22	<0.002	0.13	0.38	0.15
64.62						
S8385	100	1.52	<0.002	0.03	0.10	0.05
66.14						
S8386	100	1.53	<0.002	0.25	1.31	0.25
67.67						
S8387	100	1.52	<0.002	0.02	0.10	0.09
69.19						
S8388	100	1.53	<0.002	0.04	0.20	0.13
71.02						
S8389	100	1.52	<0.002	0.16	0.43	0.14
72.54						
S8390	100	1.52	<0.002	0.15	0.90	0.22
74.07						
S8391	100	2.13	<0.002	0.69	1.45	1.13

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BB-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 6 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI						
MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
75						
DOLOMITE	0 <> L 15 2 <> <C C+ <+ VL					
76.2						
STRONG GL WITH SD VLTS						
STRONG OXD	0 <1 <+ 0 C+ 0 <=					
76.95						
	0 <> 1 15 2 <> <C C+ <+ VL					
78.27						
SD VLTS - FAIR GL HZ PY LI	0 <= 5 <> 0 C+ <> VA					
79.55						
	0 <> 1 15 2 <> <C C+ <+ VL					
83.56						
STRONG SD VLTS <10cm WITH XL STEEL GL. SL=HZ; FAIR FRACTURE & DISSEMINATED GL≥SL	B+ <5 100 50 <D= <> <+ <+ L					
84.25						
BRECCIA - CLASTS ANGULAR <3cm, DOLOMITE≥SD. AT TOP; LOWER SECTION FINER CLASTS & SHEARED	0 C2 +2 +2 0 +4 L					
85.00						
GL COMMON AT TOP & SL AT BOTTOM						
85.55						
10 CM SD VEIN						
FAIR SD VLTS - AV 1mm; WIDELY SPACED SD VLTS WITH SL>GL	0 <1 30 1 <+ <+ 0 <C 0					
90						

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
76.20						
S8392	100	2.13	<0.002	1.45	2.14	1.99
78.33						
S8393	100	1.22	<0.002	0.45	1.06	0.59
79.55						
S8394	100	1.53	<0.002	0.36	0.66	0.48
81.08						
S8395	100	2.44	<0.002	0.74	1.22	0.52
83.52						
S8985	50	0.60	<0.002	12.80	13.70	4.80
84.12						
S8986	55	1.83	<0.002	3.18	6.02	6.98
85.95						
S8396	100	1.22	<0.002	0.71	1.37	0.69
87.17						
S8397	100	1.53	<0.002	0.04	0.08	0.05
88.70						
S8398	100	1.52	<0.002	0.04	0.06	0.02

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 7 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
90.22 – 91.70	0		<1			30	1	<4		<4		0		<C		0													
91.70 – 92.60	<1		<4				2-3	<=		<4		0		<C		0													
92.60 – 93.42	0		<4				1	<C		<C		0		DISS >		0													
93.42 – 94.79	0		<4				1	<C		<C		0		DISS >		0													
94.79 – 96.62	0		<4				1	<C		<C		0		DISS >		0													
96.62 – 98.15	0		<4				1	<C		<C		0		DISS >		0													
98.15 – 99.67	0		<4				1	<C		<C		0		DISS >		0													
99.67 – 101.19	0		<4				1	<C		<C		0		DISS >		0													
101.19 – 102.72	0		<4				1	<C		<C		0		DISS >		0													
102.72 – 104.24	0		<4				1	<C		<C		0		DISS >		0													

90.22 – 91.70: DOLOMITE

91.70 – 92.60: 3cm - 30° BAND WITH HEAVY BLEB GL WITH HALO OF <3mm SD+GL+SL VLTS

92.60 – 105: VERY WEAK SD VLTS SPACED 1-15cm. TRACES GL, SL, PY < 2mm VLTS & < 2cm BLEBS

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
90.22						
S8399	100	1.52	<0.002	0.45	0.75	0.24
91.74						
S8400	100	1.68	<0.002	1.36	2.20	0.40
93.42						
S8201	100	1.37	<0.002	0.09	0.13	0.02
94.79						
S8202	100	1.83	<0.002	0.10	0.03	0.01
96.62						
S8203	100	1.53	<0.002	0.03	0.02	0.01
98.15						
S8204	100	1.52	<0.002	0.01	<0.01	<0.01
99.67						
S8205	100	1.52	<0.002	<0.01	0.01	<0.01
101.19						
S8206	100	1.53	<0.002	0.01	0.01	<0.01
102.72						
S8207	100	1.52	<0.002	0.02	0.03	<0.01
104.24						
S8208	100	1.53	<0.002	0.03	0.01	<0.01

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 8 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT
0	<4				2	<*	<*	0	B	0						
B>	<=				20		<+	<>	0	<*	0					
0	<*				1		<*	<*	0	B	0					
0	<1					<3	<>	<>	0	<*	0					

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
105.77						
S8209	100	1.52	<0.002	0.02	0.01	0.01
107.29						
S8210	100	1.52	<0.002	0.03	0.03	0.02
108.81						
S8211	100	1.53	<0.002	0.17	0.43	0.62
110.34						
S8212	100	1.52	<0.002	0.28	0.63	0.03
111.86						
S8213	100	1.53	<0.002	0.20	0.89	0.35
113.39						
S8214	100	1.52	<0.002	0.06	0.15	0.02
114.91						
S8215	100	1.52	<0.002	0.06	0.12	0.03
116.43						
S8216	100	1.53	<0.002	0.04	0.07	0.02
117.96						
S8217	100	1.52	<0.002	0.02	0.05	0.01
119.48						

105

DOLOMITE

106.20

INCREASING SD VLTS WITH WEAK GL SL BLEB VLTS DISSEMINATED PY

112.73

65° ± ZONE - BANDS 8-25 cm SD-QZ VLTS WITH DISSEMINATED ± VLT SX

114.63

DECREASING SD VLTS - <1mm TRACES SL ± GL, MINOR GASH ± VLT PY

117.70

BANDS < 25 cm ABOUT 1/1.5m WITH 7-15% SD VLTS

120

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 9 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION: QZ MODE / AMT	SD MODE / AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE / AMT	SL MODE / AMT	HZ MODE / AMT	PY MODE / AMT	LI MODE / AMT	SAMPLING DETAILS & ASSAY RESULTS: SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
120	DOLOMITE	0	<1			3	<>	<>	0	<+	D	S8218	100	1.53	<0.002	0.17	0.29	0.07
												121.01						
121.9	35% PATCHY QZ - WEAK SD; DISSEMINATED & FRACTURE GL & HZ											S8219	100	1.52	<0.002	0.70	1.07	0.38
122.15		<>	<=		10	4	<+	<>	0	<+	D	122.53						
	INCREASED SD WITH SX VLTS, SPACED 10-20 cm, MINOR QZ-SD VLT < 5cm											S8220	100	1.52	<0.002	1.01	1.34	0.22
												124.05						
124.56												S9992	95	1.53	<0.002	2.04	3.01	0.64
	DECREASING SD VLTS WITH WEAK GL>SL	0	<>		6	2-3	<C	<C	0	D<	0	125.58						
												S8221	100	1.52	<0.002	0.95	1.37	0.37
												127.10						
												S8222	100	2.14	<0.002	0.35	0.82	0.26
125.05	TRANSITIONAL											125.24						
	BRECCIA - CLASTS 4-40mm, SUBROUNDED BLEB SD - POST BRECCIA?; SX - MATRIX CLASTS	0	B1				+1	+1	0	+>	L	S9987	95	1.52	<0.002	1.37	6.11	2.36
130.05												130.76						
	SD VLTS 7-10mm WITH FAIR-HEAVY GL & SL AT TOP & BOTTOM & < 3cm BANDS WITH FRACTURE FILLING GL>SL & SL>GL	0	<1			7	<1	<=	0	<>	0	S9988	95	1.52	<0.002	1.09	3.22	2.05
132.20												132.28						
	WEAK SD VLTS WITH TRACE GL & SL; MINOR PY VLTS	0	<>		5	1-2	<-	<-	0	<-	---	S8223	100	1.53	<0.002	0.22	0.84	0.18
												133.81						
												S8224	100	1.22	<0.002	0.12	0.49	0.09
135																		

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 10 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION: QZ MODE / AMT	SD MODE / AMT	SD WIDTH mm MIN	SD WIDTH mm MAX	SD WIDTH mm AVG	GL MODE / AMT	SL MODE / AMT	HZ MODE / AMT	PY MODE / AMT	LI MODE / AMT	SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
135												135.05						
135.55	DOLOMITE	0	<>		5	1-2	<-	<-	0	<-	0	S8225	100	1.22	<0.002	0.28	0.89	0.40
136.05	FRACTURE ZONE -45° -CHLORITE±SLICKENSIDE ON FRACTURES											136.25						
	INCREASED SD VLTS WITH STRONGER SX; 5% STRONGEST IN 3mm SD VLTS; IRREGULAR SR SD	0	<1 K	2	10	2	<+	<+	C+	<>	<F	S8226	100	1.52	<0.002	0.25	0.71	0.25
												137.77						
												S8227	95	1.52	<0.002	0.89	2.03	0.74
												139.28						
												S8228	95	1.53	<0.002	1.21	2.50	1.54
												140.82						
												S8229	100	1.52	<0.002	0.34	0.69	0.25
												142.34						
												S8230	100	1.53	<0.002	1.41	2.31	0.96
												143.87						
144.9												S8980	95	1.52	<0.002	1.92	3.59	2.31
	<12cm BRECCIA BANDS -CLASTS <1cm AND CRACKLE BRECCIA; STRONG BLEB SD; VLT± BRECCIA MATRIX SX	0	B5				+- =	+- =	0	0	I	145.39						
												S8231	100	1.22	<0.002	0.04	0.09	0.06
												146.61						
												S8232	100	1.52	<0.002	0.03	0.06	0.03
												148.13						
												S8233	100	1.53	<0.002	0.01	0.03	0.01
												149.66						
150																		

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 11 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI										
	MODE	MODE	MIN	MAX	AVG	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE
	AMT	AMT				AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT
	0	<1	8	1-3	<+	<+	0	0	N											
	0	<1	2	4	3	<E+	<E+	0	<+	N										

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S8234	100	1.52	<0.002	0.16	0.54	0.40
151.18						
S8235	100	1.52	<0.002	0.06	0.13	0.02
152.70						
S8236	100	1.22	<0.002	0.03	0.08	0.02
153.92						
S8237	100	1.83	<0.002	0.35	1.06	0.72
155.75						
S8238	100	1.22	<0.002	0.12	0.37	0.06
156.97						
S8239	100	1.53	<0.002	0.16	0.41	0.18
158.50						
S8240	100	1.52	<0.002	0.67	1.17	1.18
160.02						
S8241	100	1.52	<0.002	0.22	0.38	0.21
161.54						
S8242	100	1.53	<0.002	0.16	0.36	0.15
163.07						
S8243	100	1.83	<0.002	0.50	1.33	0.86
164.90						

150

DOLOMITE

152.10 — SHEARED CONTACT - 80°∠

DECREASING SD+SX; GL/SL FRACTURED & CRACKLE BRECCIA

154.80 — 15cm BRECCIA - 55°∠, CLASTS ANGULAR <1cm - STRONG SX

155.35

INCREASED PY - WEAK, WIDELY SPACED VLTS

156.45

157.12

INCREASED SD VLTS WITH SX

164.85 — SEE PAGE 12

165

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 12 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	SD WIDTH mm			GL	SL	HZ	PY	LI						
	MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
BRECCIA - CLASTS ANGULAR 3mm-4cm DOLOMITE SD VLTS & VEINS SX MAINLY MATRIX FILLING	10	B6				≥2	≥1	0	±+	10						
	0	<1				≥1	≥=	D	±+	L						
FAULT ZONE - 45° SHEARED & BRECCIATED STRONG CLAY																
FRACTURED WITH 2 TRACKS FAIR SD VLTS WITH PY≥HZ GL ABSENT	0	<1		20	5	0	0	DC	<>	<F						
BRECCIA, FRACTURES DISPLACE SD VLTS																
DECREASED SD VLTS, OCCASIONAL QZ BLEBS & VLTS CUT BY SD VLTS	<> B	<+		10	3	<-	0	<-	<>	VF						
10 cm SD VEIN OXD PY COATED BY LI																
FAIR-MOD SD VLTS; WIDELY SPACED QZ VLTS; STRONG OXD; WEAK GL≥HZ; PY>GL≥HZ	<+	<1 B		30	1-6	DC	0	DC	<>	VF						

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
165						
S8243	95	1.52	<0.002	3.09	7.10	2.79
166.35						
166.80						
S8244	95	1.53	<0.002	0.15	0.48	0.48
168.25						
S8245	95	1.52	<0.002	0.04	0.08	0.12
169.77						
170.55						
S8246	45	3.05	<0.002	0.06	0.24	0.36
172.82						
173.63						
S8247	100	1.53	<0.002	0.02	0.04	0.20
174.35						
S8248	100	1.52	<0.002	<0.01	0.01	0.09
175.87						
176.5						
S8249	100	1.52	<0.002	0.06	0.06	0.77
177.39						
S8250	100	1.53	<0.002	0.07	0.07	1.43
178.92						
S8251	100	1.53	<0.002	0.03	0.05	0.48
180						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 13 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

| DESCRIPTION | ALTERATION & MINERALIZATION | | |

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 14 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
	0		V2		1	30	5	0		0		0		0		K													
	0		K			5	2-3	0		0		0		D		K													
	V2		V3			50	40	0		0		0		K		D+													
	K		V1			10	2-5	0		0		0		K		D*													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
195.68						
S8261	100	1.53	<0.002	<0.01	<0.01	<0.01
197.21						
S8262	100	1.52	<0.002	<0.01	<0.01	<0.01
198.73						
S8263	100	1.52	<0.002	<0.01	<0.01	0.02
200.25						
S8264	100	1.53	<0.002	<0.01	<0.01	0.01
201.78						
S8265	100	1.52	<0.002	<0.01	<0.01	0.02
203.30						
S8266	100	1.53	<0.002	0.01	<0.01	0.08
204.83						
S8267	100	1.52	0.002	0.01	<0.01	0.03
206.35						
S9805	100	1.52	0.002	<0.01	<0.01	0.06
207.87						
S9806	100	1.53	0.002	0.06	0.01	0.50
209.40						

195

DOLOMITE

200.9

TCM. SD VLTS; 2-5cm QZ-SD VLTS & BLEBS

202.6

DECREASING QZ & SD VLTS, SD VLTS WITH PY-LI & MINOR HZ

208.95

QZ-SD & SD VEINS; STRONG OXD. FAIR LI

209.45

210

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-1

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 15 OF 15

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

210 — DOLOMITE

MODERATE SD VLTS WITH WEAK PY. OCCASIONAL QZ & QZ-SD VLTS

212.77 — UP TO 12cm QZ-SD & ≤ 5cm SD VEINS

213.6 — VEINS WITH DISSEMINATED - MASSIVE PY-LI. STRONG COATING ANCLESITE

214.25 — SD VLTS, OCCASIONAL SR & BLEBBY; MINOR QZ ASSOCIATED WITH SD VLTS. PY IN SD VLTS CONCENTRATED IN 5-25 cm BANDS

222.59 — END OF HOLE

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI											
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
210	<		V	1	—	10	2-5	0		0		0		D<	1	0											
213.6	<		<	1		10	3-5	0		0		0		D<	1	D<	1										

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S9807	100	1.52	<0.002	0.01	0.02	0.14
210.92						
S9808	100	1.53	<0.002	0.06	0.02	0.05
212.45						
S9991	95	1.52	<0.002	0.07	0.10	0.08
213.97						
S9809	100	1.52	<0.002	0.03	0.05	0.04
215.49						
S9810	100	1.52	<0.002	<0.01	0.03	0.03
217.02						
S9811	100	1.52	<0.002	0.03	0.06	0.04
218.54						
S9812	100	1.53	<0.002	0.03	0.02	0.03
220.07						
S9813	100	1.52	<0.002	0.10	0.03	0.26
221.59						

PROJECT NDU-BLENDE
COORDINATES 20003.32N, 10279.37E
HOLE ANGLE -50°
LOGGED BY M.P. PHILLIPS

TARGET 5 627 ZONES
AZIMUTH 335°
FINAL DEPTH 244.14m

CORE SIZE NQ -0-214.27m; BQ 214.27-244.14m
ELEVATION 1796.16m
DATE STARTED JULY 10 1988

HOLE NUMBER B-88-2
PAGE 1 OF 17
DATE FINISHED JULY 15 1988

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION																						SAMPLING DETAILS & ASSAY RESULTS								
		QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI								No. SAMPLE end INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn		
		MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT								
0	CASING - NON CORING																															
5.18	DOLOMITE WEAK SD VLTS	0	<4					2	0		0		0		0		0															
8.84	BLEACHED, 1CM SD, GL, HZ																								8.84							
8.95	HEAVY LI, MINOR GL VLTS COATING HZ; BRECCIA																															
9.40																																
9.60																																
9.90	B & 10 CM BANDS POROUS LI, MINOR GL, COATING HZ	0	<3						0		0		0		0		<F								S9993	92	1.52	<0.002	10.80	21.2	6.41	
	WEAK SD VLTS																								10.36							
																									S9994	95	1.53	<0.002	0.31	0.84	0.91	
12.0																									11.89							
12.57	POROUS LI, REMNANT GL & COATING HZ	0	<3						D		0		CC		0		PH								S9995	95	1.52	0.007	1.43	5.42	7.74	
13.33		0	<3						0		0		0		0		<F								13.41							
14.03	POROUS LI, REMNANT GL	0	<C						D		0		CC		0		PH								S9996	95	1.53	<0.002	3.85	9.82	16.30	
14.60		0	<3						0		0		0		0		<F															
15.00	HEAVY POROUS LI	0	0						0		0		0		0		PH								14.94							

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 2 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

15

15.72 — 13cm HEAVY POROUS LI, MINOR GL — DOLOMITE

WEAK SD VLTS

17.07 — 17cm HEAVY LIMONITE

17.43

17.55 — HEAVY LI, MINOR GL COATING HZ

21.95 — 30% 2-10cm BANDS LI MINOR GL + HZ

22.56

22.95 — DOWN SECTION SD VLTS & SX GENERALLY FRESH

SD VLTS WITH SX SPACED 1/10-100cm

27.50 — 3cm SD VLT TO 1cm VLTS GL, LI & HZ

29.96 — LI, BRECCIATED, REMNANT DISSEMINATED & BLEB GL

29.26

29.45 — SK & VLT SD, 10cm BAND CRYSTALLINE GL

LI, 1-2cm DOLOMITE CLASTS IN SD MATRIX, BLEB GL WEAK HZ

29.85 — CONTACT 3

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI						
	MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
	0 <1			30	2-3	0	0	0	0	<E						
	<1	<1	—	—	—	D+	0	C+	0	PL						
	0 <1			30	2-3	0	0	0	0	<F						
	0 <1		1	5	1-2	<1 D+	0	DC	D-	<F						
	10 10 H	1 1	—	15	—	D2 M4 B+	0 0	C- 0	0 0	PA <L PA						

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S997	95	1.52	<0.002	0.47	1.51	1.86
16.46						
S998	100	1.52	<0.002	0.52	1.63	0.81
17.98						
S999	100	1.53	<0.002	0.07	0.17	0.41
19.51						
S1000	100	1.52	<0.001	<0.01	0.03	0.08
21.03						
S9171	98	1.53	<0.002	0.34	0.95	1.39
22.56						
S9172	100	1.52	<0.002	0.17	0.39	1.00
24.08						
S9173	100	1.52	<0.002	0.16	0.23	0.74
25.6						
S9174	100	1.53	<0.002	0.13	0.44	0.61
27.13						
S9175	100	1.52	<0.002	0.44	1.30	0.42
28.65						
S9176	100	1.53	<0.002	6.27	15.30	7.29

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 3 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI										
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
30																				
30.35	0	<2						<+	0	DC	D	<F								
STRONGLY BRECCIA <1cm CLASTS DOLOMITE																				
GL DISSEMINATED, BLEB & VLT																				
31.12	0	+1						DD +	0	CC	0	PH								
SD VLTS 1-20mm, GL FRESH, SL TO BY SD WITH SX, 1-20-30 cm SPACING																				
	0	<+	1	20	<5	<D	0	DC	0	<F										
40.70																				
BRECCIA-ANGULAR <3cm CLASTS IN SD MATRIX WEAK SX, FRESH SL	<1	+3				<D	<+	0		L										
41.83																				
INCREASED SD VLTS <1cm WITH GL>PY>SL, WEAK OXD.	0	<2		10		<+	<+	0	<+	<L										
43.55																				
<2cm BRECCIA BANDS WITH WELL MINERALIZED <1cm SD VLTS	0	<+				<C	<D	0	<+	0										
44.70																				
SEE PAGE 4 FOR DESCRIPTION					SEE		PAGE	4												
45																				

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
30.18						
S9177	100	1.52	<0.002	3.24	9.00	13.20
31.70						
S9178	100	1.52	<0.002	0.31	0.76	2.53
33.22						
S9179	100	1.53	<0.002	0.35	0.91	1.01
34.75						
S9180	100	1.52	<0.002	0.36	0.85	0.82
36.27						
S9181	100	1.53	<0.002	0.38	0.70	0.52
37.80						
S9182	100	1.52	<0.002	0.79	1.68	1.18
39.32						
S9183	95	1.52	<0.002	0.67	1.57	2.00
40.84						
S9184	98	1.53	<0.002	0.74	1.17	4.82
42.37						
S9185	100	1.52	<0.002	1.95	3.13	1.83
43.89						
S9186	100	1.52	<0.002	3.53	5.72	2.92

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 4 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

45.

STRONG BRECCIA - ANGULAR 2mm DOLOMITE
2cm STRONG BLEB SD STRONG
SL GL & PY

46.70

48.10

CONTACT: TRANSITIONAL STRONG BRECCIA
ANGULAR CLASTS 3mm-5cm SD CLASTS

48.17

60% 15 cm SD VEIN AT UPPER CONTACT

48.17

SD VLTS SPACED 1-20-50cm APART WITH GL MINOR PY2 TRACES SL WEAK OXIDATION

54.70

40% SD VLTS - 5mm-5cm WITH GL7 SL7 PY

55.25

56.50

BRECCIA

56.73

SD VLTS <3mm DECREASING TOWARDS LOWER CONTACT

58.00

MINERALIZED SD VLTS 5mm-30mm WIDE ABOUT 1 METRE SPACING

60

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI
	MODE / AMT	MODE / AMT	MIN	MAX	AVG	MODE / AMT	MODE / AMT	MODE / AMT	MODE / AMT	MODE / AMT
	0	B =				+ =	+ +	0	+)	0
	0	< +				< C	<)	0	< +	0
	0	+ B 2				+ ±	+ =	0	+)	< L
	0	< +				< C	<)	0	< +	0
	D	< 1	1	20		< +	<)	0	<)	0
	0	< 4	5	50		< 2	< =	0	<)	0
	0	< 1	1	20		< +	<)	0	<)	
	0	+ ±				+ 2	+ ±	0	+ =	0
	0	<)				< +	< +		< C	
	0	<)		< 30	1-2	< +	< C	0	< +	0

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
45.41						
59187	100	1.53	<0.002	6.56	10.20	4.69
46.94						
59188	100	1.52	<0.002	4.05	6.30	4.42
48.46						
59189	100	1.53	<0.002	1.46	2.17	2.96
49.99						
59190	100	1.83	<0.002	0.60	0.90	0.46
51.82						
59191	100	1.52	<0.002	2.51	3.29	1.76
53.34						
59192	100	1.52	<0.002	1.90	3.36	2.53
54.86						
59193	100	1.53	<0.002	0.87	1.87	2.15
56.39						
59194	100	1.52	<0.002	1.21	2.40	2.03
57.91						
59195	100	1.53	<0.002	0.51	1.02	0.41
59.44						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 5 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

| VISUAL LOG | DESCRIPTION | ALTERATION & MINERALIZATION | | |

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 6 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
75.29						
S9606	90	1.52	<0.002	15.30	18.30	6.12
76.81						
S9607	80	1.52	<0.002	15.80	23.40	7.55
78.33						
S9608	80	1.53	<0.002	0.57	0.72	0.88
79.86						
S9609	90	1.52	<0.002	3.88	5.44	3.56
81.38						
S9610	90	1.53	<0.002	2.30	4.06	4.98
82.91						
S9611	100	1.52	0.002	8.46	13.80	7.67
84.43						
S9612	100	1.52	<0.002	12.10	20.30	7.17
85.95						
S9613	100	1.52	<0.002	7.15	13.90	2.55
87.48						
S9614	100	1.52	<0.002	3.91	8.37	2.55
89.0						
S9615	100	1.53	<0.002	7.44	16.60	6.20

75.66 — SEE BOTTOM PAGE 5 — DOLOMITE

BRECCIATED SHEARED CLASTS SUBROUNDED 2-15mm AV < 5mm GL FRESH TO LEACHED PY & SL LEACHED

77.25 — HIGHLY FRACTURED OXIDIZED WEAK GL, WEAK SD VLTS <1-2mm

79.25 — CRUSHED FAULT ZONE

80.00 — MOD. FRACTURED FAIR OXIDIZED WEAK SD WITH SX

WEAK SD & SX

82.08 — BRECCIA 5-30cm BANDS WITH 3-10mm CLASTS STRONG LEACHED, SD VLTS & BRECCIA MATRIX

83.15 — VLTS <2mm SL

83.65 — BRECCIA CLASTS ANGULAR 3-10mm BLEACHED HIGHLY OXIDIZED, MIDDLING 15cm NON BRECCIA

84.43 — BRECCIA CLASTS 2-20mm ANGULAR TO SUBROUNDED <8cm BANDS FINE CRYSTALLINE-SEMI GNEISSIC GL

84.70 — BRECCIA - WEAK CLASTS BLEACHED; SX & SD VLTS & BRECCIA MATRIX; GL - SEMI GNEISSIC, WEAK BLEB QZ

85.20 — SD VLTS <1cm; GL VLTS 1/20cm SPACING

85.53 — TWO - 15cm BANDS SEMI GNEISSIC GL

86.13 — 88.20 — 89.15 — 90

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 7 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	SD WIDTH mm			GL	SL	HZ	PY	LI						
	MODE	AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
90																
	*	<D*				<D	D=	0	D1	⊥	—					
91.15																
	0	<+	<5	2-3	<+	<*	0	<>	L							
94.30																
	0	<+		1-2	<-	<*	0	<>	_0							
95.10																
95.50																
97.0																
	0	<*		<1	0	<C	0	<*	0							
103.42																
103.75																
105																

BRECCIA 3-2cm ANGULAR IN PLACES DOLOMITE ≤5mm ROUNDED-CRUSHED CLASTS 5%- MAINLY PY FAIR DARK SL ± MINOR GL

WEAK SD VLTS

WEAK SD VLTS WITH GL UNDER SL ± PY

FAIR SD VLTS WITH PY > SL > GL

20% SD VLTS 5-20 cm

SD VLTS ≤1mm WITH PY, MINOR PY VLTS, WEAK LI ex PY

INCREASED SD VLTS - OCC WEAK PY ± SL

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
90.53						
S9616	100	1.52	<0.002	0.25	0.59	3.26
92.05						
S9617	100	1.52	<0.002	0.28	0.63	0.34
93.57						
S9618	100	1.53	<0.002	0.45	1.01	0.33
95.10						
S9619	100	1.52	—	<0.01	0.03	0.05
96.62						
S9620	100	1.53	-	0.01	0.03	0.01
98.15						
S9621	100	1.52	-	0.01	0.03	0.01
99.67						
S9622	100	1.52	-	0.01	0.03	0.02
101.19						
S9623	100	1.53	-	<0.01	0.03	0.02
102.72						
S9624	100	1.52	-	<0.01	0.01	0.04
104.24						
S9625	100	1.53	-	<0.01	0.02	0.04

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 8 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

105

105.70 DOLOMITE

106.10 11cm SD VEIN - MINOR QZ — SD VLTS WITH TRACE PY, CL, SL

108.80

109.4 20% SD VLTS <5mm AV 2mm WITH GL > PY

111.80 SD VLTS - WEAK PY & GL

117.30 INCREASED SD VLTS <3mm AV 1-2mm

118.45 INCREASED SX ASSOCIATED WITH 1mm-10mm SD VLTS SD+SX VLTS ~ 1/10-15cm; RARE GL ON FRACTURE

120

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI															
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
	0	<*					<1	0	<C			0	<*	0																	
	0	<+					1-3	<C	<C			0	<C	0																	
					1	5	1-2	<C	0			0	<C	L																	
	0	<=			3		1-2	<*	<*				<C																	
	BC	<1	L		10			<+	<+			0	<>	L																	

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
105.77						
S9626	100	1.52	-	0.15	0.55	0.11
107.29						
S9627	100	1.52	-	0.13	0.40	0.05
108.81						
S9628	100	1.52	-	0.20	0.25	0.05
110.33						
S9629	100	1.53	-	0.38	0.41	0.07
111.86						
S9630	100	1.53	-	0.07	0.11	0.06
113.18						
S9631	100	1.52	-	0.11	0.23	0.08
114.91						
S9632	100	1.52	-	0.06	0.07	0.05
116.43						
S9633	100	1.53	-	0.06	0.10	0.04
117.96						
S9634	100	1.52	-	0.19	0.63	0.18
119.48						
S9635	100	1.53	-	0.29	0.78	0.15

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER B-88-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 9 OF _____

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
120																													
	0	<1			1	5	1-2	<1		0		0		<1		L													
121.25																													
	0	<1				2	1	<1		<1		0		0		L													
135																													

SEE BOTTOM PAGE 8

DOLOMITE

WEAK SD VLTS <2mm WITH WEAK SX

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
121.01						
S9636	95	1.52	-	0.10	0.16	0.13
122.53						
S9637	85	1.52	-	<0.01	0.02	0.01
124.05						
S9638	100	1.53	-	<0.01	0.01	0.01
125.58						
S9339	100	1.52	-	<0.01	0.01	0.01
127.10						
S9640	85	1.53	-	0.02	0.01	0.01
128.63						
S9641	95	1.52	-	0.01	0.02	0.01
130.15						
S9642	85	1.52	-	<0.01	0.01	0.01
131.67						
S9643	100	1.53		<0.01	0.02	0.01
133.20						
S9644	95	1.52		0.01	0.02	0.01
134.72						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 10 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION											SAMPLING DETAILS & ASSAY RESULTS						
		QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI		SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
		MODE	MODE	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT								
135	DOLOMITE	D	<1		2	1	<=	<=	0	0	L								
													S9645	95	1.53	-	<0.01	0.02	0.01
													136.25						
													S9646	100	1.52	-	<0.01	0.01	<0.01
													137.77						
													S9647	100	1.52	-	<0.01	0.02	0.01
													139.29						
													S9648	95	1.52	-	0.04	0.03	0.02
													140.81						
													S9649	100	1.53	-	0.03	0.08	1.04
142.15																			
	INCREASED FRACTURING & SD VLTS WITH INCREASED SD VLTS SL>GL>PY	B+	<1		50		<+	<=	0	<>	0								
													142.34						
													S9650	95	1.53	-	0.07	0.11	0.82
144.10													143.87						
	SD VEINS UP TO 10cm WITH WEAK SX RARE GL & SL IN <3 mm SD VLTS	B+	<=		100	<3	<<	<<	0	<-	0		S9672	95	1.52	-	0.29	2.03	1.41
													145.39						
													S9673	95	1.52	-	0.16	1.08	0.35
146.80																			
	INCREASED SD VLT; SX ASSOCIATED WITH 5mm SD VLTS	B+	<3		30	20	<=	<-	0	<>	L								
													S9674	100	1.53	-	0.28	1.90	1.34
148.20													148.44						
	DECREASED SD; SX MAINLY FRACTURE FILLING. GL>SX	BC	<1		40	3	<+	<+	<>	F									
													S9675	95	1.52	-	0.26	1.48	0.67
150													149.96						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 11 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

| VISUAL LOG | DESCRIPTION | ALTERATION & MINERALIZATION | | |

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 12 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION																				SAMPLING DETAILS & ASSAY RESULTS							
		QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI												
		MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT											
165.05	DOLOMITE	0	<1	<1		1	3		<1		<1		0		<1		0												
	INCREASED SD VLTS WITH SX																												
168.35	VUGGY SD VLTS; OCCASIONALLY FILLED WITH SX WEAK SL	0	<1					1-2	<1		<1		0		<1		0												
177.50	PY VLTS - ENVELOPE SD																												
178																													
180																													

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
165.20						
S9690	100	1.53	<0.002	0.31	0.50	1.59
166.73						
S9691	100	1.52	<0.002	0.06	0.16	0.17
168.25						
S9692	92	1.52	<0.002	0.04	0.06	0.05
169.77						
S9693	100	1.53	<0.002	0.02	0.05	0.03
171.30						
S9694	100	1.52	<0.002	0.03	0.08	0.23
172.82						
S9695	100	1.53	<0.002	0.07	0.16	0.37
174.35						
S9696	100	1.52	<0.002	0.09	0.13	0.04
175.87						
S9697	100	1.52	<0.002	0.04	0.10	0.03
177.39						
S9751	95	1.53	<0.002	0.03	0.06	0.02
178.92						
S9752	90	1.52	<0.002	<0.01	0.05	0.02

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 13 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
180																													
DOLOMITE	0	<1%				1-2	<-	<<	Q	<<	0																		
182.35																													
182.65 2-4% SD VLTS																													
183.79																													
INCREASD SD VLTS WITH SX MINOR CP	B>	K=	1	10	1-3	K+	K+	0	<>			CP	D+																
186.70																													
INCREASED SD VLTS	0	<1		30	3-5	K+	K=	0	<>			CP	DC																
188.50																													
188.89 STRONG FRACTURES WITH SLICKENSIDE, WEAK GASH SD VLTS																													
FAULT ZONE - MOSTLY SHEARED AT TOP, BRECCIA <5mm CLASTS; NEAR LOWER CONTACT TRACES PY, GL>SD, BLEACHED	0	K+					<<	0		0		<<	D																
MAIN BREAK - 5 ZONE																													
191.80 KNIFE LIKE BREAK 50% - SHEARED SX	PB	K+					K+							K>															
192.32 STRONG QZ FLOODING																													
WEAK BRECCIA - <3cm BANDS - WEAK SX, MOSTLY PY	B>						K<	0		0				K>		D													
192.74 BRECCIA - CLASTS 2-20mm WEAK SD, SX-PY>GL, MINOR SL																													
193.13	K+	K+					K+1	K>	0	0	K+2					CP	DC												
193.55 7cm BAND - 40% SX																													
CRACKLE FRACTURING WEAK SD WITH MINOR SX VEINLETS WEAK	<-	<<					K-	0		0	K-																		
194.10																													
NEAR UC 13cm SD>BA>QZ VEIN WITH SX, QZ VEINLETS																													
VEIN AT LC - SEMI MASSIVE PY>GL WEAK SL	V=	N6					V1	V+	0	N2						CP	DC												
IN DOLOMITE SD>BA																													
195																													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
180.94						
59753	100	1.53	<0.002	0.06	0.09	0.03
181.57						
59754	100	1.52	<0.002	0.10	0.23	0.27
183.49						
59755	100	1.52	<0.002	0.39	1.17	0.21
185.01						
59756	100	1.53	<0.002	0.82	1.60	0.20
186.54						
59757	90	1.52	<0.002	0.32	0.91	0.74
188.06						
59758	95	1.53	<0.002	1.08	0.52	0.33
189.59						
59759	85	1.52	<0.002	0.19	1.20	0.41
191.11						
59760	95	1.53	<0.002	0.27	1.14	0.59
192.63						
59761	95	1.53	<0.002	0.98	3.32	1.22
194.16						
59762	100	1.52	<0.002	0.83	3.14	0.72

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 14 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION: QZ MODE / QZ AMT	SD MODE / SD AMT	SD WIDTH mm MIN	SD WIDTH mm MAX	SD WIDTH mm AVG	GL MODE / GL AMT	SL MODE / SL AMT	HZ MODE / HZ AMT	PY MODE / PY AMT	LI MODE / LI AMT	SAMPLING DETAILS & ASSAY RESULTS: SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
195																		
195.5	SEE PAGE 13																	
	DOLOMITE	<-	<C				<-	0	0	<=	L							
195.99	STRONG GL WITH SD VLTS	0	<1	3	15	5	<1	<+	0	<=	L							
196.40		<-	<C				<-	0	0	<-	L							
197.20		<C	<>				<+	<C	0	<+	0	-195.68						
	CRACKLE FRACTURING DECREASES. TRACES GL IN FRACTURES ± SD VLTS											S9763	95	1.53	<0.002	0.08	0.31	0.13
												-197.21						
												S9764	95	1.52	<0.002	0.06	0.27	0.11
												-198.73						
												S9765	95	1.52	<0.002	0.04	0.23	0.09
200.40	BRECCIA BANDS <4cm, STRONG SD-QZ	B2 <2	<1				+2	+1	0	+2	0	-200.25						
200.85	STRONG OOLITIC PY±SD-BRECCIA?	<1	<3				B <=	0	0	<3	L	S9766	90	1.53	<0.002	0.66	1.51	2.70
201.55	CONTACT 40°x	V2	V1		20	<5	<=	<+		<1	L	CP 0.1%						
	ZONES <40cm WITH SR ± 2cm QZ > SD VLTS; SD X-CUT QZ VLTS PY > GL > SL VLTS ≤ 5mm; ASSOCIATED WITH WEAK SD TRACES CC ± CP											-201.78						
												S9767	100	1.52	<0.002	0.54	0.93	1.13
												-203.30						
205.0	WEAK SD VLTS WITH MINOR SX	0	<+				<C	<C	0	<C	L	S9768	100	1.53	<0.002	0.58	0.77	0.75
												-204.83						
												S9769	90	1.52	<0.002	0.23	0.41	0.69
206.4	BANDS 2-8 cm BRECCIA MATRIX PY > GL, MINOR SL	0	B1				++	+>	0	+2	L	-206.35						
206.7	10 cm BAND BRECCIA-MATRIX SD, HZ ± TRACE GL	0	<+				<C	<C	0	<C	L	S9770	100	1.52	<0.002	0.98	1.87	2.06
206.9												-207.87						
207.25	TO 15cm SD VLTS WITH SX	0	<1				<>	<+	0	<1	L							
207.75		B+	<1				<+	<+	0	M2 <2	0	S9771	95	1.83	<0.002	2.73	3.44	3.65
208.05	2-15 cm BANDS OF SEMI-MASSIVE PY-OOLITIC ± CRYSTALLINE											-209.78						
209.25	SD VLTS ± SX, WEAK SX	0	<=	1	10	2-4	<C	<C	0	<-	0							
210																		

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 15 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION																				SAMPLING DETAILS & ASSAY RESULTS							
		QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI											SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
		MODE	MODE	MIN	MAX	AVG	MODE	MODE	MODE	MODE	MODE	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT							
							AMT	AMT	AMT	AMT	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT							
210																												
210.25	60% 2-6cm BANDS SEMI-MASSIVE SX	B	B1		40		<2	<1	0	<2	d	PO										59772	95	1.22	<0.002	1.90	2.42	2.22
210.6	STRONG VLT±SK SD, WEAK SX	0	<K	1	10	2-4	<C	<C	0	<-	0											210.92						
																						59773	95	1.53	<0.002	0.09	0.06	0.57
212.2	5cm SD VEIN - 20% PY	B+	K2				<4	<4	0	<4	0											212.45						
213.0	DECREASING SK SD OCCASIONAL SD VLT WITH STRONG SX		<1																			59774	85	1.52	<0.002	0.39	0.08	2.06
214.4																						213.97						
	2-6cm SD VEINS WITH PY±HZ	0	<B1				0	0	C1	<2	<1											59775	90	1.22	<0.002	0.45	0.13	2.70
215.18		B+	<1				<4	<4	0	<4	0											215.19						
																						59776	100	1.52	<0.002	0.04	0.02	0.16
																						216.71						
																						59777	100	1.53	<0.002	0.03	0.01	0.08
																						218.24						
																						59778	80	1.52	<0.002	0.06	0.02	0.08
219.40	15cm BAND HEAVY LIMONITE																					219.76						
	FAIR SD VLTS	<C	<=	1	10	3-4	0	0	0	<4	<F											59779	100	1.52	<0.002	0.03	0.02	0.10
																						221.28						
																						59780	100	1.53	<0.002	0.04	0.02	0.38
223.25																						222.81						
	SD VLTS±VEINS (1-12cm) WITH WEAK PY MINOR < 2mm QZ VLTS, IN PLACES STRONGLY OXIDIZED	<C	<1				0	0	0	<D	VF											59781	100	1.83	<0.002	0.10	0.06	0.85
224.60																						224.64						
225		<C	<=	1	10	3-4	0	0	0	<4	<F																	

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 16 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT
<C		<=		1	10	3-4	0		0		0		<1		<F	
<1		<>			5	2	0		0		0		0-1		0	

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
59782	100	1.52	<0.002	0.34	0.01	0.03
226.16						
59783	100	1.53	<0.002	0.04	0.01	0.07
227.69						
59784	100	1.52	<0.002	0.07	0.03	1.02
229.21						
59785	100	1.52	<0.002	0.05	0.04	0.48
230.73						
59786	100	1.53	<0.002	0.04	0.01	0.06
232.26						
59787	100	1.52	<0.002	0.04	0.01	0.03
233.78						
59788	90	1.53	<0.002	0.06	0.04	0.17
235.31						
59789	90	1.52	<0.002	0.03	0.01	0.19
236.83						
59790	100	1.52	<0.002	0.01	<0.01	0.06
238.35						
59791	100	1.53	<0.002	0.03	0.01	0.19
239.88						

225

DOLOMITE

229.73

WEAK SD VLTS UP TO 10cm
QZ-SD VEINS SPACED 1.3m

233.8

HIGHLY FRACTURED

235.5

237.7

12cm SD VEIN -1% PY ± LI

240

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 17 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT
	<1		<1		5	2		0		0		0		Tr		0

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
59792	100	1.52	<0.002	0.03	<0.01	0.04
241.90						
59793	100	1.53	<0.002	<0.01	0.01	0.04
242.93						
59794	95	1.21	<0.002	<0.01	0.01	0.08
244.14						

240.0

240.22 — 5cm QZ-SD VEIN-SD CORE±QZ ENVELOPE — DOLOMITE

243.25 — 10cm QZ-SD VEIN — SD CORE±QZ ENVELOPE — OXIDIZED

244.14 — END OF HOLE

PROJECT NDU-BLENDE
COORDINATES 20003.32N, 10279.37E
HOLE ANGLE -70°
LOGGED BY

TARGET 5 & 7 ZONES
AZIMUTH 001°
FINAL DEPTH 253.50m

CORE SIZE NQ 0-55.17m; BQ 55.17-116.43m; AQ 116.43-253.50
ELEVATION 1796.16m
DATE STARTED JULY 15 1988

HOLE NUMBER 88-B-3
PAGE 1 OF 17
DATE FINISHED JULY 20 1988

SCALE 1:100

VISUAL LOG	DESCRIPTION	ALTERATION & MINERALIZATION																						SAMPLING DETAILS & ASSAY RESULTS								
		QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI								SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn		
		MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT								
0	CASING - NON CORING																															
3.66	MOD. OXIDIZED ON FRACTURES & SD VLTS — DOLOMITE	0	<1%					<1	0		0		0		0		≤F								3.66								
4.63	LIMONITE - DARK BROWN — WEAK SD VLTS																PH															
4.82	BRECCIA - CLASTS ANGULAR 3-30mm - HIGHLY OXIDIZED	0	<2						+		0		C+		0		+M															
5.35	LIMONITE - BOXWORK - DARK REDDISH BROWN	0	0						0		0		C+		0		PH															
5.55	SD VLTS to 1cm	0	<1			10			<+		0		<C+		0		<M								5.18								
	BRECCIA? - HIGHLY OXIDIZED																								59815	65	1.53	<0.002	7.87	14.30	4.15		
																									6.71								
																									59816	65	1.52	<0.002	1.84	2.88	2.75		
8.23																									8.23								
8.60	FRACTURED DOLOMITE - MOD. OXIDIZED — LIMONITE - DARK REDDISH BROWN - MINOR GL	0	0						DC		0		DC		0		PH															
		0	<+						0		0		0		0		<F								59817	77	1.52	<0.002	3.79	9.45	5.49		
9.35																									9.75								
9.65		0	0						DC		0		DC		0		PH															
	FAIR OXIDATION ON FRACTURES — WEAK SD VLTS	0	<=						<4		0		<2		0		≤F								59818	77	1.53	<0.002	0.16	0.33	0.62		
11.0																									11.28								
	HIGHLY FRACTURED & OXIDIZED	0	<1%						0		0		0		0		<L															
12.50																																	
	FAULT ZONE - STRONG OXIDIZED	0	0						0		0		0		0		<L								59819	60	3.05	<0.002	0.10	0.43	1.49		
14.33																									14.33								
15		0	<=						<2		0		<2		0		<F															

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BR-B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 2 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI						
	MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
15	0	<=				<>	0	<>	0	<E						
DOLOPUTE																
17.47																
BRECCIA 1cm ANGULAR CLASTS MATRIX SD±GL	0	±1				++	0	C·	0	<F						
18.0																
BRECCIA - HIGHLY PITTED & LEACHED 2.5cm BANDS GL WITH COATING AG	0	+2				+1	± =	0	0	PH						
19.C																
LOWER CONTACT 30x/																
SD VLTS OXIDATION ON FRACTURES WEAK	0	<>			1-2	0	0	0	0	<F						
23.47																
23.77																
SD VLTS 45mm WITH WEAK GL±HZ																
26.52																
DOWN SECTION - INCREASED SD+Sx VLTS	0	<=	3	10	5	<D>	0	<C D	<C	<L						
29.56																
STRONG SK SD VLTS <4cm																
29.96																

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S9820	67	3.04	<0.002	0.80	2.84	1.26
17.37						
S9821	100	1.53	<0.002	10.20	24.6	11.80
18.90						
S9822	100	1.52	<0.002	0.98	4.12	0.48
20.42						
S9823	100	1.53	<0.002	0.12	0.54	0.34
21.95						
S9824	100	1.52	<0.002	0.07	0.27	0.35
23.47						
S9825	100	1.52	<0.002	0.06	0.16	0.50
24.99						
S9826	100	1.53	<0.002	0.31	0.55	0.85
26.52						
S9827	100	1.52	<0.002	0.87	1.60	1.43
28.04						
S9828	100	1.53	<0.002	0.92	1.78	1.77
29.57						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 3 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI											
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
30																											
30.6 DOLOMITE	0		<=		3	10	5	<>	DI	0		<>	D	<>		VL											
SK SD VLTS GL	0		<6					BD	+	0		0		DC		PM											
31.33																											
10-30cm BANDS SK SD WITH GL	0		<1			10		<>	D	0		0		0		<M											
34.23																											
	0		<=		3	10	5	<>	D	0																	
36.80																											
FAIR SD VLTS WITH GL,SL HZ & LI	0		<1		1	5	3	<>		<*		0		0		<F											
39.83																											
	0		<>	B		10	3	<*		<*		0		<.		<L											
WEAK SD VLTS WITH GL,SL & PY																											
43.90																											
INCREASED SD VLTS WITH GL,SL HZ & LI IN 20-25 cm BANDS	0		<1		3	25	3-4	D	N+	0		D.		0		<F											
45																											

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
59829	100	1.52	<0.002	5.02	8.21	8.67
31.05						
59830	100	1.52	<0.002	2.10	3.92	6.20
32.61						
59831	100	1.53	<0.002	0.45	1.17	1.62
34.14						
59832	100	1.52	<0.002	0.51	1.28	1.26
35.66						
59833	100	1.53	<0.002	0.26	0.62	0.58
37.19						
59834	100	1.52	<0.002	0.22	0.46	0.38
38.71						
59835	100	1.52	<0.002	0.76	1.31	0.19
40.23						
59836	100	1.53	<0.002	0.35	0.77	0.26
41.76						
59837	100	1.52	<0.002	0.16	0.30	0.50
43.28						
59838	100	1.53	<0.002	2.74	4.47	4.41
44.81						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-B-2

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 4 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

45 SEE PAGE 3 — DOLOMITE

45.45

45.65 STRONG SD VLTS - VLTS < 5mm — WEAK SD VLTS

46.12 STEEL GL

47.18 SK SD VLTS

47.60

49.38 DOWNSECTION INCREASED SD±SX VLTS

50.9 INCREASED SD VLTS WITH GL, SL±HZ

51.77

52.63 INCREASED SD+GL VLTS

53.15 8cm BRECCIA±SD - LOWER CONTACT 45°

WIDELY SPACED <5mm SD VLTS WITH STRONG GALENA

55.17

INCREASED SD+3X VLTS
SD VLTS - 2 SET STRONG 70°
±WEAKER LOW°
FAIR OXIDATION

59.82
60

ALTERATION & MINERALIZATION

	OZ		SD		WIDTH mm			GL		SL		HZ		PY		LI															
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
45–45.45	0		<1		3	25	13+	D+		0		D·		0		<F															
45.45–45.65	0		<3		4	25		D	1	0		0		0		DM															
45.65–46.12	0		<>					<C		0		0		DC																	
46.12–47.18																															
47.18–47.60																															
47.60–49.38																															
49.38–50.9																															
50.9–51.77	0		<=		2	10	3	<D+		D<*		<*		D·		<DF															
51.77–52.63	0		<>					<C		0		0		DC		D															
52.63–53.15	0		<1			15	1	D>		0		DC		0		VF															
53.15																															
53.15–55.17	0		<>					<C		0		0		DC		0															
55.17–59.82	0		<1		1	10	3-5	<D+		<>		C*		0		VF															

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
59835	100	1.52	<0.002	3.91	6.23	2.34
46.33						
59840	100	1.52	<0.002	1.92	2.78	3.05
47.85						
59841	100	1.53	<0.002	0.69	0.98	0.48
49.38						
59842	100	1.52	<0.002	0.64	0.90	0.67
50.9						
59843	100	1.53	<0.002	2.33	3.44	1.24
52.43						
59844	100	1.52	<0.002	1.84	3.40	3.97
53.95						
59845	100	1.22	<0.002	0.51	0.99	0.46
55.17						
59846	100	1.83	<0.002	1.25	2.24	0.76
57.00						
59847	100	1.52	<0.002	2.68	8.00	1.76
58.52						
59848	100	1.53	<0.002	1.84	4.71	1.80

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88 R-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 5 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI						
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
60																		
60.4																		
DOLOMITE	0	<1						<<C	0	0	DC	0						
SD-SX FLOODED SX ABSENT	0	<6						0	0	0	0	<1						
60.88																		
61.49	0	<=	1	10				>>D	0	0	0	VL						
3cm SD FLOODED																		
INCREASED SD+SX VLTS	0	<1	2	30	10	<>D	<>	D%	DC	VF								
62.40																		
WEAK SD VLTS & SX	0	<>	1	10	2	<C	<C	0	<C	VL								
65.89																		
BRECCIA-ANGULAR 2-15mm CLASTS	0	+/-	1			+/-	+=	0	0	<1								
66.16																		
STRONG MATRIX GL±SL																		
WEAK SD VLTS;	0	<+				<1	<=	0	<+	0								
VLTS GL-SL COMMON																		
67.0	0	<>		10	2	<C	<C	0	<C	VL								
68.35																		
68.78	0	<+	2	25	3	+/+	+/+	0	+/>	VL								
8 CM BRECCIA-HEAVY SX																		
WIDE SPACED (3-15cm) SD VLTS WITH HEAVY SX																		
MODERATE DISSEMINATED & FRACTURE SX																		
71.50	0	<>	1	5	2	<C	<-	0	<-	VL								
WEAK SD VLTS & WEAK SX																		
75																		

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
60.05						
S9849	100	1.52	<0.002	0.47	0.91	0.44
61.57						
S9850	100	1.52	<0.002	0.36	1.17	0.85
63.09						
S9851	100	1.52	<0.002	0.04	0.41	0.16
64.62						
S9852	100	1.52	<0.002	2.34	4.28	2.05
66.14						
S9853	100	1.53	<0.002	3.91	5.26	1.56
67.67						
S9854	100	1.52	<0.002	2.51	3.09	0.98
69.19						
S9855	100	1.52	<0.002	2.22	2.42	1.08
70.71						
S9856	100	1.53	<0.002	2.92	3.14	1.54
72.24						
S9857	100	1.52	<0.002	0.34	0.41	0.32
73.76						
S9858	100	1.53	<0.002	0.10	0.21	0.17

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BB B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 6 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH mm MIN	WIDTH mm MAX	WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT
0	<>	<>	1	5	2	<>	<-	0	<-	VL						
<+	<-	<=	1	10	4	<+	<<	0	<>	VL						
0	<>	<>	1	5	2	<<	<-	0	<-	VL						
<>	<+	<+	3	10	5	<+ D	<> D	0	<>	VL						
0	<>	<>	1	5	2	<<	<-	0	<-	VL						
0	<-	<=	1	10	2	<+	<>	0	<>	VL						

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
75.25						
S9859	100	1.52	<0.002	0.44	0.66	0.27
76.81						
S9860	100	1.52	<0.002	0.78	1.17	0.55
78.35						
S9861	100	1.53	<0.002	0.47	0.75	0.20
79.86						
S9862	100	1.52	0.002	1.20	1.48	0.65
81.38						
S9863	100	1.53	<0.002	0.08	0.17	0.14
82.91						
S9864	100	1.52	<0.002	2.51	2.84	0.44
84.43						
S9865	100	1.52	<0.002	4.61	4.62	1.39
85.95						
S9866	100	1.53	<0.002	3.27	3.08	0.92
87.48						
S9867	100	1.52	<0.002	1.21	1.32	0.30
89.00						
S9868	100	1.52	<0.002	3.67	4.52	0.78

DOLOMITE
WEAK SD VLTS & SX

78.53
INCREASED SD VLTS & SX
78.12

80.30
TO 20cm BANDS, INCREASED SD VLTS WITH FAIR-HEAVY SX

82.13

83.30
BANDS SPACED 15-30cm APART WITH INCREASED SD VLTS & SX FAIR FRACTURE GL

87.95

89.48
TO 10MM SD VLTS - MOD-STRONG GL/SL
HIGHER PY THAN NORMAL

90

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BBR-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 7 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI							
	MODE	MODE	MIN	MAX	AVG	MODE	MODE	MODE	MODE	MODE							
	AMT	AMT				AMT	AMT	AMT	AMT	AMT							

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
90.52						
S9869	100	1.53	<0.002	12.00	13.40	6.82
92.05						
S9870	100	1.52	<0.002	5.83	13.70	6.71
93.57						
S9871	100	1.53	<0.002	1.46	6.13	3.41
95.10						
S9872	100	1.52	<0.002	0.07	0.14	0.06
96.62						
S9873	100	1.53	<0.002	0.09	0.10	0.07
98.15						
S9874	100	1.52	<0.002	0.23	0.23	0.17
99.67						
S9875	100	1.52	<0.002	0.17	0.19	0.05
101.19						
S9876	100	1.53	<0.002	0.07	0.11	0.03
102.72						
S9877	100	1.52	<0.002	0.06	0.10	0.01
104.24						

90

90.48

91.43

94.03

94.33

105

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88 B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 8 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI									
	MODE	MODE	MIN	MAX	AVG	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE
	AMT	AMT				AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S3878	100	1.52	<0.002	0.07	0.13	0.01
105.76						
S9879	100	1.53	<0.002	0.10	0.21	0.02
107.29						
S9880	100	1.52	<0.002	0.13	0.25	0.02
108.81						
S9881	100	1.52	<0.002	0.17	0.22	0.06
110.33						
S9882	100	1.53	<0.002	0.03	0.10	0.02
111.86						
S9883	100	1.53	<0.002	0.15	0.16	0.03
113.39						
S9884	95	1.52	<0.002	0.08	0.20	0.06
114.91						
S9885	100	1.52	<0.002	0.19	0.36	0.11
116.43						
S9886	100	1.53	<0.002	0.73	0.91	0.18
117.96						
S9887	100	1.52	<0.002	50.3	25.8	9.67
119.48						

105

DOLOMITE

111.30

DOWNSECTION INCREASED
SD VLTS, OCC BLEB & FRACTURE PY

112.90

FRACTURES 0-30° & WITH WEAK SLICKENSIDE

116.43

116.76

BRECCIA - CLASTS SUBANGULAR-SUB ROUNDED 2mm-2cm
NO INCREASE IN SX

117.20

BRECCIA - AS ABOVE

118.20

118.35

WEAK STHEARED ~45° X CONTACT

BRECCIA ZONE

GL - MASSIVE & BRECCIA FILLING
SD - BLEBS TO 3cm CLASTS
30% BRECCIA IN < 10cm BANDS
STRONG SX

119.52

120

SEE PAGE 9

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI
	MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
	0	B2				X4	+2	+C	+D	PL
	0	++				M=	++	0	+Y	CL

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88 B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 9 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

WIDTH mm

	QZ MODE	QZ AMT	SD MODE	SD AMT	WIDTH MIN	WIDTH MAX	WIDTH Avg	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	LI MODE	LI AMT
120.0																	
MAINLY MASSIVE GL IN BRECCIA — DOLOMITE-BRECCIA ZONE	<>		B+					M6	X+			O		D+		VL	
120.87																	
ANGULAR 2-20mm CLASTS	D		<C					+ +		++		D		++		VL	
PY HIGHER THAN NORMAL			+														
WEAK SX																	
121.90																	
WEAK SD VLTS & SX	O		B+					+ + <		+ > <		D		+ + <		< L	
122.85																	
123.33																	
3-10 cm. BRECCIA BANDS-STRONG SX-GL/SL																	
124.70																	
BRECCIA-STRONG MATRIX SX																	
125.89																	
IN PLACES WEAK SHEARED-20% OCCASIONAL 2-5cm BANDS BRECCIA & CRACKLE BRECCIA WITH INCREASED SX	<>		<>		1	100	5	+ > <		+ + <		O		+ + <		L	
128.75																	
BRECCIA-BLEB & MATRIX SX																	
129.30																	
131.80																	
TRANSITIONAL- CLASTS 5-30mm, BLEB SD	D		B2					+ +		+ =		+ >		+ >		L	
132.30																	
STRONG SX TRANSITIONAL	<>		<>		1	100	5	+ > <		+ + <		O		+ + <		L	
134.35																	
135																	

SEE PAGE 10

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
59888	100	1.53	<0.002	18.30	31.90	9.02
121.01						
59889	100	3.04	<0.002	5.98	7.64	1.52
124.05						
59890	100	2.44	<0.002	5.83	7.79	2.59
126.49						
59891	100	1.53	<0.002	1.37	2.27	0.92
128.02						
59892	100	1.67	0.003	4.26	6.14	4.76
129.68						
59893	100	1.37	<0.002	2.25	4.38	3.28
131.06						
59894	90	1.83	<0.002	5.42	9.32	4.56
132.89						
59895	100	1.53	<0.002	2.27	4.56	0.86
134.42						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88-5-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 10 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI										
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
135.17		<1		<1	1	100	5	<+	<+	0	<+	L								
136.60		0		<+				<-	<-	0	<C	VF								
141.65		0		<1				<C	<C	0	<C	VF								
146.82		0		<+				<-	<-	0	<C	VF								
149.10		0		<1	1	10	3.5	<+	<+	0	<-	L								
150																				

BRECCIA

DOLOMITE

VERY WEAK SD VLTS ± SX, INCREASED SUPERGENE ALTERATION ON FRACTURES

CRACKLE ± BRECCIA ZONE SLIGHT INCREASE IN SX 10% TO 40cm BANDS NON-BRECCIATED, FAIR SUPERGENE ALTERATION;

INCREASED SD VLTS ± SX; SD VLTS MOSTLY <45° x; FLATTER SD VLTS BETTER MINERALIZED; CLAY FILL ON FRACTURES

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S9896	100	1.52	<0.002	3.32	5.34	2.30
135.64						
S9897	100	2.13	<0.002	0.26	0.43	0.13
138.07						
S9898	100	1.22	<0.002	0.03	0.06	0.04
139.29						
S9899	95	1.53	<0.002	0.26	0.50	0.05
140.82						
S9900	95	1.52	<0.002	0.34	1.14	0.85
142.34						
S8301	95	1.52	0.002	0.51	1.12	0.92
143.86						
S8302	95	1.53	0.002	0.31	0.54	2.06
145.39						
S8303	95	1.52	0.004	0.06	0.13	0.15
146.91						
S8304	100	1.53	0.002	0.10	0.16	0.16
148.44						
S8305	100	1.52	<0.002	0.48	1.03	0.82
149.96						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BRE-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 11 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
	0	<1			1	10	3-5	<+		<+		0		<-		L													
	0	<1						+C		+C		+C		+C		VF													
	0	B=			-	-		+1		++		0		+C		VL													
	<C	<1			1	10	5	<*		<+		0		<C		0													

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
SB306	100	1.53	0.002	0.58	1.31	1.04
151.48						
SB307	85	1.52	<0.002	0.64	1.39	0.44
153.01						
SB308	100	3.05	<0.002	1.46	1.66	0.35
156.06						
SB309	100	1.52	<0.002	1.15	2.68	1.43
157.58						
SB310	100	1.53	<0.002	0.22	0.52	0.57
159.11						
SB311	100	1.52	<0.002	0.74	1.34	0.21
160.63						
SB312	100	1.52	<0.002	0.34	0.54	0.61
162.15						
SB313	100	1.53	<0.002	0.23	0.45	0.43
163.68						
SB314	100	1.52	<0.002	0.22	0.46	0.09

150.

DOLOMITE

BRECCIA, CRACKLE & SHEAR ZONE
SHEARS 30°x ; BRECCIAS ALONG
SHEARS ; WEAK SD.

153.20

STRONGER BRECCIA & SHEARS
INCREASED BLEB SD WITH SX

157.0

WEAK SD VLTS WITH SX VLTS
SPACED 10-30 CM APART ; SL & GL

157.55

165

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER BBR-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 12 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

QZ MODE	QZ AMT	SD MODE	SD AMT	SD WIDTH mm MIN	SD WIDTH mm MAX	SD WIDTH mm AVG	GL MODE	GL AMT	SL MODE	SL AMT	HZ MODE	HZ AMT	PY MODE	PY AMT	L1 MODE	L1 AMT
<*	<>				4		<-		<>		0		<-			
		<+		1	100	25	<*		<+		0		<(		0	
<>		<=		1	20	3-5	<<		<<		0		<-		<L	

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
165.20						
S8315	100	1.53	<0.002	0.08	0.14	0.68
166.73						
S8316	100	1.52	<0.002	0.03	0.05	0.21
168.25						
S8317	100	1.52	<0.002	0.04	0.07	0.46
169.77						
S8318	100	2.44	<0.002	0.07	0.10	0.48
172.21						
S8319	100	2.75	<0.002	0.12	0.17	0.82
174.96						
S8320	100	2.43	<0.002	0.06	0.06	0.77
177.39						
S8321	100	2.14	<0.002	0.04	0.10	0.32
177.53						

165
165.10

DOLOMITE
MAINLY < 4mm SD VLTS WITH MAINLY FINE HONEY COLORED; COARSE GRAINED DARK COLORED SL INCREASED QZ VLT AV. 1cm

172.10

INCREASED SD VLTS; DECREASED SX

176.5

FRACTURED OCC WEAK BRECCIATED; INCREASED SD VLT DECREASED SX

180

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 13 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

| VISUAL LOG | DESCRIPTION | ALTERATION & MINERALIZATION | | |

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88 E-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 14 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT
195			DOLOMITE																										
	0	<1			1	2	1-2	<1		<1		0		0		VL													
196.52																													
	SD VLTS TO 5cm																												
	FAIR SLTHZ/CL																												
197.22	0	<2				50		<1		<1		<1		<1		VL													
	<1	<1			1	3	1	<1		<1		0		<1		0													
203.0																													
	WEAK SHEARING ON																												
	FRACTURES 0-20°																												
204.15																													
206.38	17mm BAND TO 1cm SD VLTS																												
210																													

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
S8331	100	1.52	<0.002	0.01	0.06	0.06
196.29						
S8332	100	2.13	<0.002	0.03	0.06	0.07
198.42						
S8333	100	1.53	<0.002	<0.01	0.18	0.34
199.95						
S8334	100	1.68	<0.002	0.03	0.16	0.14
201.63						
S8335	100	1.67	<0.002	0.10	0.29	0.38
203.3						
S8336	100	2.44	<0.002	0.04	0.23	0.11
205.74						
S8337	100	1.52	<0.002	0.05	0.22	0.35
207.26						
S8338	85	1.22	<0.002	0.04	0.22	0.17
208.48						
S8339	83	1.83	<0.002	0.01	0.08	0.23

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88E-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 15 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI							
	MODE AMT	MODE AMT	MIN	MAX	AVG	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT	MODE AMT
210 – 213.7 DOLOMITE	<C	<4	1	3	1	<C	<C	0	<1	0							
213.7 – 214.0 HIGHLY BROKEN FAULT ZONE																	
214.0 – 214.2 BRECCIA-SD BLEBS-SX-MAINLY PY-10%																	
214.2 – 216.5 FRACTURED																	
216.5 – 217.0 SD VLTS TO STOCKWORK CONCENTRATED IN < 15 cm BANDS. WEAK GL/SL FAIR FINE FRACTURING	0	<1	1	20	4	<-	<-	0	<-	<T							
217.0 – 225 DOWNSECTION INCREASED FRACTURING																	

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
210.31						
58340	76	2.14	<0.002	0.02	0.05	0.18
212.45						
58341	83	1.82	<0.002	0.13	0.55	0.38
214.27						
58342	77	2.75	<0.002	0.03	0.10	0.04
217.02						
58343	86	1.52	<0.002	0.01	0.10	0.03
218.54						
58344	68	3.05	<0.003	0.03	0.16	0.02
221.59						
58345	60	3.05	<0.002	0.04	0.25	0.01
224.64						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 16 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

ALTERATION & MINERALIZATION

	QZ		SD		WIDTH mm			GL		SL		HZ		PY		LI													
	MODE	AMT	MODE	AMT	MIN	MAX	AVG	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT	MODE	AMT

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
225						
225.15 DOLOMITE						
HIGHLY BROKEN & VERY FINE BRECCIA - FAULT ZONE						
227.32						
SLIGHT INCREASE IN SD. VLTS; STRONGER SX						
S8346	40	3.05	<0.002	0.18	0.50	0.50
227.69						
S8347	82	3.04	<0.002	0.80	2.37	2.77
230.73						
S8348	80	1.83	<0.002	0.38	0.62	1.15
232.56						
GASH & VLT SD; TRACE-WEAK SX						
S8349	90	1.22	<0.002	0.07	0.09	0.25
233.78						
S8350	75	1.22	<0.002	0.03	0.07	0.02
235.0						
S8351	88	2.13	<0.002	0.16	0.35	0.08
237.13						
S8352	88	1.22	<0.002	0.04	0.10	0.10
237.95 SD VLTS TO 7mm FAIR SLYGL						
238.35						
S8353	64	2.75	<0.002	0.06	0.12	0.13
240						

PROJECT _____ TARGET _____ CORE SIZE _____ HOLE NUMBER 88B-3

COORDINATES _____ AZIMUTH _____ ELEVATION _____ PAGE 17 OF 17

HOLE ANGLE _____ FINAL DEPTH _____ DATE STARTED _____ DATE FINISHED _____

LOGGED BY _____

SCALE 1:100

VISUAL LOG

DESCRIPTION

240

DOLOMITE

245.57

STOCKWORK SD-50%
PY>GL>SL

246.98

INCREASED SX
PY>SL>GL

247.50

BND OF HOLE

253.50

ALTERATION & MINERALIZATION

	QZ	SD	WIDTH mm			GL	SL	HZ	PY	LI						
	MODE	MODE	MIN	MAX	AVG	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE	MODE
	AMT	AMT				AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT	AMT
	0	<> D	1	5	3	D-	D-	0	D-	L						
	0	KS				D+	D+	0	D+	0						
	0	<+				E> *	E>	0	E+	0						
	0	<> D	1	5	3	D-	D-	0	D-	L						

SAMPLING DETAILS & ASSAY RESULTS

SAMPLE No. and INTERVAL	% RECOVERY	SAMPLE WIDTH	oz/t Au	oz/t Ag	% Pb	% Zn
241.10						
S8354	31	4.87	<0.002	0.18	0.25	0.98
245.97						
S8355	88	1.53	<0.002	1.48	2.10	2.77
247.50						
S8356	88	1.52	<0.002	0.22	0.33	0.40
249.02						
S8357	90	1.53	<0.002	0.17	0.22	0.57
250.55						
S8358	85	1.52	<0.002	0.04	0.06	0.07
252.07						
S8359	95	1.52	<0.002	<0.01	<0.01	<0.01
253.50						



PALEOZOIC

- Pc — light grey weathering dolomite

LATE PROTEROZOIC ?

- + + — gabbro and diorite

LATE PROTEROZOIC

PINGUICULA GROUP

- P3 — dark shale and siltstone with narrow conglomerate bed near base
- P2 — red weathering stromatolitic dolomite
- P1 — dark siliceous siltstone and fine sandstone with thin dolomitic mudstone interbeds

MIDDLE PROTEROZOIC

GILLESPIE LAKE GROUP

- G2 — buff orange to brown weathering stromatolitic dolomite with minor dolomitic mudstone
- G1 — maroon or green weathering mudstone with light orange weathering dolomitic interbeds

QUARTET GROUP

- Q2 — black slate, phyllite and argillite

- high angle fault
- thrust fault
- mineralized outcrop or head of talus train
- 1988 diamond drill hole
- 28,142 (T 24805) — Archer, Cathro soil sample location with sample number plus Pb and Zn values in ppm
- X 18,156 (T 24818) — Archer, Cathro stream sediment sample location with sample number plus Pb and Zn values in ppm
- ⊗ 89,270 — GSC stream sediment sample location with Pb and Zn values in ppm
- 0.06,0.25,0.38 (M 53375) — Archer, Cathro rock sample location with sample number plus Pb and Zn assays in % and Ag in g/t
- 26,50 (K 7488) — Archer, Cathro rock sample location with sample number plus Pb and Zn values in ppm
- area of grid soil response exceeding 1000 ppm Pb

Figure 5

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

GEOLOGICAL AND GEOCHEMICAL COMPILATION

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:10,000

0 100 200 300 400 500 1000 Metres
0 500 1000 2000 3000 Feet

To accompany report dated December, 1989

220
106 D 7
092745


P2
P1
Pc
G2
G1
Q2
P3
FOOTWALL P1
MAIN FAULT
ZONE 10
ZONE 11
ZONE 12
ZONE 13
ZONE 14
ZONE 15
ZONE 16
ZONE 17
ZONE 18
ZONE 19
ZONE 20
ZONE 21
ZONE 22
ZONE 23
ZONE 24
ZONE 25
ZONE 26
ZONE 27
ZONE 28
ZONE 29
ZONE



LEGEND

PALEOZOIC

P_c — light grey weathering dolomite

LATE PROTEROZOIC?

gabbro and diorite

LATE PROTEROZOIC

PINGUICULA GROUP

P_3 — dark shale and siltstone with narrow conglomerate bed near base

P_2 — red weathering stromatolitic dolomite

P_1 — dark siliceous siltstone and fine sandstone with thin dolomitic mudstone interbeds

MIDDLE PROTEROZOIC

GILLESPIE LAKE GROUP

G_2 — buff orange to brown weathering stromatolitic dolomite with minor dolomitic mudstone

G_1 — maroon or green weathering mudstone with light orange weathering dolomitic interbeds

QUARTET GROUP

Q_2 — black slate, phyllite and argillite

high angle fault

thrust fault

geological contact

V-5m — stockwork or breccia zone with width and dip if known

V-0.6m — narrow vein with width and dip if known

mineralized talus train

X — mineralized float

88-01 — diamond drill hole with hole number

CP	chalcopyrite
CA	calcite
GL	galena
HZ	hydrozincite
L I	limonite
MC	malachite
PY	pyrite
QZ	quartz
SD	siderite
SL	sphalerite

□ chip sample location with Pb(%), Zn (%), Ag (g/t), Cu (%) / interval (m)

■ rock specimen location with Pb (%), Zn (%), Ag (g/t), Cu (%)

(n.a.– not analyzed)

1984 Systematic Chip Sampling

A — continuous chip sample with grades shown below

> 9 % Pb + Zn

5 – 9% Pb + Zn

< 5 % Pb + Zn

Sample Location	True Width (m)	Pb (%)	Zn (%)	Ag g/t
A	23.0	2.7	1.6	27.4
B	31.3	2.6	1.2	44.6
C	11.9	7.8	2.1	120.0
D	35.1	0.5	1.7	10.3
E	30.6	0.8	4.1	27.4
F	47.3	1.6	4.3	30.9
G	21.4	1.9	2.2	27.4
H	21.5	1.2	3.6	20.6
I	25.0	3.4	6.1	61.7
J	28.0	3.7	3.0	130.3

Figure 9

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

DETAILED GEOLOGY AND MINERALIZATION

BLENDE PROPERTY
(WEST SHEET)

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:2000

0 50 100 150 200 Metres
0 100 200 300 400 500 600 Feet

To accompany report dated December, 1989

092795



LEGEND

PALEOZOIC

- Pc — light grey weathering dolomite

LATE PROTEROZOIC?

- gabbro and diorite

LATE PROTEROZOIC
PINGUICULA GROUP

- P3 — dark shale and siltstone with narrow conglomerate bed near base
- P2 — red weathering stromatolitic dolomite
- P1 — dark siliceous siltstone and fine sandstone with thin dolomitic mudstone interbeds

MIDDLE PROTEROZOIC
GILLESPIE LAKE GROUP

- G2 — buff orange to brown weathering stromatolitic dolomite with minor dolomitic mudstone
- G1 — maroon or green weathering mudstone with light orange weathering dolomitic interbeds

QUARTET GROUP

- Q2 — black slate, phyllite and argillite

- high angle fault
- thrust fault
- geological contact
- minor shear zone
- foliation attitude with dip
- stockwork or breccia zone with width and dip if known
- narrow vein with width and dip if known
- mineralized talus train
- chip sample location with Pb(%), Zn(%), Ag(g/t), Cu(%) / interval (m)
- rock specimen location with Pb(%), Zn(%), Ag(g/t) and Cu(%)

CP	chalcopyrite
CA	calcite
GL	galena
HZ	hydrozincite
LI	limonite
MC	malachite
PY	pyrite
QZ	quartz
SD	siderite
SL	sphalerite

Figure 10

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

DETAILED GEOLOGY AND MINERALIZATION

BLENDE PROPERTY
(EAST SHEET)

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:2000

0 50 100 150 200 Metres
0 100 200 300 400 500 600 Feet

To accompany report dated December, 1989

- soil sample
x silt sample
□ chip sample
■ rock specimen

Figure 14

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

SAMPLE LOCATIONS

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:5000
0 50 100 200 300 400 500 Metres
0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989



soil sample location with lead value in ppm

- ≥ 5000 ppm
- ≥ 2000 ppm – < 5000 ppm
- ≥ 1000 ppm – < 2000 ppm
- ≥ 500 ppm – < 1000 ppm
- ≥ 200 ppm – < 500 ppm

diamond drill hole

high angle fault

thrust fault

mineralized outcrop or head of talus train

Figure 15

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

LEAD GEOCHEMISTRY

BLENDE PROPERTY (293)

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

106 D 7

SCALE 1:5000

0 50 100 200 300 400 500 Metres

0 100 500 1000 1500 Feet

To accompany report dated December, 1989

092755

LOCATION MAP



.134 soil sample location with zinc value in ppm

≥ 5000 ppm

≥ 2000 ppm – < 5000 ppm

≥ 1000 ppm – < 2000 ppm

≥ 500 ppm – < 1000 ppm

diamond drill hole

high angle fault

thrust fault

mineralized outcrop or head of talus train

Figure 16

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

ZINC GEOCHEMISTRY

BLENDE PROPERTY (294)

NDU RESOURCES LTD.
BILLITON METALS CANADA INC. 106 D 7

SCALE 1:5000

0 50 100 200 300 400 500 Metres

0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989



soil sample location with silver value in ppm

≥ 10 ppm

≥ 5 ppm - < 10 ppm

≥ 2 ppm - < 5 ppm

diamond drill hole

high angle fault

thrust fault

mineralized outcrop or head of talus train

Figure 17

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

SILVER GEOCHEMISTRY

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:5000
0 50 100 200 300 400 500 Metres
0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989

APPROXIMATE PROPERTY BOUNDARY - BLENDE 1-122 CLAIMS

Unmineralized Cap Rock

℄ 21 000 N

℄ 20 000 N

℄ 19 000 N

9 000 E

10 000 E

11 000 E

12 000 E

13 000 E

14 000 E

APPROXIMATE PROPERTY BOUNDARY - BLENDE 1-122 CLAIMS

- soil sample location with copper value in ppm
- ≥ 200 ppm
- ≥ 100 ppm - < 200 ppm
- ≥ 50 ppm - < 100 ppm
- diamond drill hole
- high angle fault
- thrust fault
- mineralized outcrop or head of talus train

Figure 18

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

COPPER GEOCHEMISTRY

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:5000
0 50 100 200 300 400 500 Metres
0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989

APPROXIMATE PROPERTY BOUNDARY — BLENDE 1-128 CLAIMS

APPROXIMATE PROPERTY BOUNDARY — BLENDE 1-102 CLAIMS

Unmineralized Cap Rock

soil sample location with arsenic value in ppm

≥ 200 ppm

≥ 100 ppm - < 200 ppm

≥ 50 ppm - < 100 ppm

diamond drill hole

high angle fault

thrust fault

mineralized outcrop or head of talus train

Figure 19

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

ARSENIC GEOCHEMISTRY

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:5000

0 50 100 200 300 400 500 Metres

0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989



LEGEND

- Thrust fault
- High angle fault
- 1988 diamond drill hole
- Mineralized outcrop or head of talus train

Contour interval: 10% vertical in phase of primary field

Figure 20

ARCHER, CATHRO & ASSOCIATES (1981) LIMITED

FRASER FILTERED VLF

BLENDE PROPERTY

NDU RESOURCES LTD.
BILLITON METALS CANADA INC.

SCALE 1:5000

0 50 100 200 300 400 500 Metres

0 100 500 1000 1500 Feet

092795

To accompany report dated December, 1989