MAP NO.:	**ASSESSMENT REPORT**	X	**DOCUMENT NO:** 092882
	PROSPECTUS		**MINING DISTRICT:** WHITEHORSE
105 L 15	**CONFIDENTIAL**	X	**TYPE OF WORK:** Diamond Drilling
	OPEN FILE		

REPORT FILED UNDER: DROMEDARY EXPLORATION COMPANY LTD

DATE PERFORMED: JUNE 10-29, 1990 **DATE FILED:** OCT 25, 1990

LOCATION: **LAT.:** 62°55'N **AREA:** Dromedary Mountain

LONG.: 135°15'W **VALUE $:**

CLAIM NAME & NO.: NORA 1-34
ACE 7-12,23-28,39-44,55-60,70-76,85-87,89-92,105-108
ACE 121-124,137-140,153-156,169-172,277-284,293-300,309-316

WORK DONE BY: Aurum Geological Consultants Inc.

WORK DONE FOR: Dromedary Exploration Company Ltd.

DATE TO GOOD STANDING:	

REMARKS: Three diamond drill holes were attempted on the property, two of which were successful. The holes intersected argillites, graphitic argillites, chert breccias and limy sandstones. Sulphides included pyrrhotite, pyrite, sphalerite and galena. Massive sulphites including 80% pyrr, 5-10% py, and 10-15% silica with galena in fract. returned 2.98% Pb, .49% Zn, >100 ppm Ag and 145 ppb Au. The massive sulphides are bedded and occur over 4.8 meters.

Affairs Canada

no.

R.M.M.R. file no.

Date forwarded
25 OCT 1990

TRANSMITTAL FORM

OFFICE OF THE REGIONAL MANAGER
MINERAL RIGHTS
OCT 25 1990
WHITEHORSE
YUKON TERRITORY

From ▶ Mining Recorder at: Whitehorse

To ▶ Regional Manager, Mineral Rights at Whitehorse, Y.T.

For action are:

☐ NEW APPLICATION FOR PLACER LEASE TO PROSPECT	Name		
☐ RENEWAL APPLICATION PLACER LEASE TO PROSPECT	Name	Lease no.	
☐ AFFIDAVIT OF EXPENDITURE ON PLACER LEASE	Name	Lease no.	
☐ SECURITY DEPOSIT			
☐ FINANCIAL ABILITY			
☐ ASSIGNMENT OF PLACER LEASE NO.	From	To	
☐ GROUPING APPLICATION UNDER SEC. 52(2) PLACER MINING ACT.	Owner		
☑ DIAMOND DRILL LOGS	Claims: ACE, NORA	Claim sheet no.: 105-L-15	
☐ QUARTZ ASSESSMENT REPORT	Claims	Claim sheet no.	
	Type of report	Submitted by: ALRUM GEOLOGICAL CONS. INC.	
	Cls. work performed on	$ req. for ren. application	

M Southwick
Signature

Date returned

REPLY ACTION

092882

Noted Nov 21/90

Signature

802-37 (7-88)

1990 ASSESSMENT WORK ON THE ACE AND NORA CLAIM GROUP

Whitehorse M.D., Yukon Territory
May 29 - September 25, 1990

Claims:

Ace 7-12, 23-28	YA52061-066, 077-082
Ace 39-44, 55-60	YA52093-098, 109-114
Ace 70-76, 85,87	YA51443-449, 458,460
Ace 89-92	YA51462-464
Ace 105-108, 121-124	YA52127-130, 143-146
Ace 137-140, 153-156	YA52159-162, 175-178
Ace 169-172, 277-284	YA52191-194, 335-141
Ace 293-300, 309-316	YA52352-358, 367-374
Nora 1-34	YB26763-796

Location:
1. 240 km N of Whitehorse, Yukon Territory
2. NTS Sheet 105L/15
3. Latitude 62° 55'N
   Longitude 135° 15'W

For:
Dromedary Exploration Company Ltd.
935-800 West Pender Street
Vancouver, B.C.
V6C 2V6

092882

By:
R. Hulstein, B.Sc., FGAC
Aurum Geological Consultants Inc.
412-675 West Hastings Street
Vancouver, B.C.
V6B 1N2

October 22, 1990

This report has been examined by the Geological Evaluation Unit under Section 53 (4) Yukon Quartz Mining Act and is allowed as representation work in the amount of $_____.

for Regional Manager, Exploration and Geological Services for Commissioner of Yukon Territory.

AURUM GEOLOGICAL CONSULTANTS INC.

October 22, 1990
Whitehorse, Yukon

Mr. R. H. Whittingham
Mining Recorder
Whitehorse Mining District
Room 201, Federal Building
Whitehorse, Yukon Territory
Y1A 2B5

Dear Sir;

Re: 1990 assessment work on the Ace and Nora claim group (Quartz Mining Act), NTS 105L-15.

Please find enclosed maps, drill sections, drill logs, statement of costs, and analytical results from work carried out on the Dromedary Project. Two diamond drill holes, totalling 434.64 meters, were successfully completed by Kluane Drilling Ltd. An additional hole was lost in overburden at 15.00 meters. All the core was logged by Craig Hart, B.Sc. of Aurum Geological Consultants Inc. Selected intervals were logged and sampled by Glen Shevchenko of Placer Dome Inc. who also drafted the cross sections.

Mobilization was by fixed wing to the Clear Lake airstrip located approximately 20 km to the south of the project site, from airstrips located at Carmacks, Minto and Pelly Crossing and then by BELL 206 helicopter to the drill site. Diamond drilling started on June 10 and and was completed on June 29, 1990. Diamond drill hole 90-1 was collared on the Ace 310 (YA52368) claim and DDH90-2, plus the unsuccessfull hole, were collared on the Ace 277 (YA52335) claim. The drill, a LONGYEAR 34, has been left on site at DDH90-2 to facilitate an early start-up in 1991.

I trust the enclosed information will meet the 1990 assessment requirements as filed by Aurum Geological Consultants Inc. on behalf of Dromedary Exploration Company Ltd.

Sincrely,
Aurum Geological Consultants Inc.



Roger Hulstein, B.Sc., FGAC

412 ~~604~~ 675 West Hastings Street,
Vancouver, B.C.,
Canada V6B 1N2
Tel: (604) 683-9656
Fax: (604) 683-7625

P.O. Box 5179,
Whitehorse, Yukon,
Canada Y1A 4S3
Tel: (403) 667-4168
Fax: (403) 668-2021

TABLE OF CONTENTS

PROPERTY LOCATION MAPS



DROMEDARY EXPLORATION CO. LTD.

DROMEDARY PROJECT

WHITEHORSE MINING DISTRICT

LOCATION

Aurum Geological Consultants Inc.	MARCH 1990
NTS 105 L/14	DRAWN BY NH
SCALE 1:1,000,000	FIGURE: 1



DROMEDARY EXPLORATION COMPANY LTD

DRILL HOLE LOCATIONS

SCALE 1:50,000

OCT. 10/90

RWH

AURUM GEOLOGICAL CONSULTANTS INC.



CLAIM STATUS AS OF OCTOBER 19, 1990

CLAIM NAME	GRANT #	EXPIRY DATE*
Ace 7-12	YA52061-066	May 1, 1996
Ace 23-28	YA52077-082	May 1, 1996
Ace 39-44	YA52093-098	May 1, 1996
Ace 55-60	YA52109-114	May 1, 1996
Ace 70-76	YA51443-449	May 1, 1996
Ace 85,87	YA51458,460	May 1, 1996
Ace 89-92	YA51462-464	May 1, 1996
Ace 105-108	YA52127-130	May 1, 1996
Ace 121-124	YA52143-146	May 1, 1992
Ace 137-140	YA52159-162	May 1, 1992
Ace 153-156	YA52175-178	May 1, 1992
Ace 169-172	YA52191-194	May 1, 1992
Ace 277-284	YA52335-141	May 1, 1996
Ace 293-300	YA52352-358	May 1, 1996
Ace 309-316	YA52367-374	May 1, 1996
Nora 1-34	YB26763-796	May 1, 1995

*Subject to approval of 1990 assessment work.

DROMEDARY EXPLORATION COMPANY LTD.
ACE AND NORA CLAIMS, WHITEHORSE MINING DISTRICT

092882

CLAIM MAP & DRILL HOLE LOCATION

Date: Oct. 19, 1990 NTS: 105L/15
By: R.W.H.
Aurum Geological Consultants Inc.

FIGURE # 2

MAP#105L/15 Doc#092882 (242)

DIAMOND DRILL LOG

DDH90-1

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 1 of 8

Property DROMEDARY | NTS 105 L / | Claim ACE 310 | Elevation 2150' | Azimuth 018 (GRID NORTH) | Length 274.62 | Dip -47°

Coordinates L 61+87 W 9+30S | Dip Tests 33.5, 137.2 + EOH (PAGE 8) | Advance | Depth | Date Collared 10 JUNE | Date Completed 19 JUNE

Purposes INTERSECT COINCEDENT MAG, GRAV, VLF + HLEM ANOMALIES | Drilled by KLUANE | Assays by NAL | Logged by C. HART

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py	% Po	Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
0	20.11			OVERBURDEN - incl black silicified mudstone with extensive qtz veining, green-grey greywacke and tan coloured chert.											
20.11	24.84			Black carbonaceous/graphitic phyllite with extensive (30% by volume) calcite veining. Cleavage surfaces (S1) are shiney + soft. Brittle fractures @ 50-55°. Rock is generally limey. Bedding is folded + contorted. Sporadically distributed py - all secondary (2°) but some smeared out along brittle fractures (F1). Some blebs of 5% py	1-2										
24.84	27.95			Significantly harder + more competent core. Silicified dk grey sandstone grades after 0.5m to dk. grey pyritic argillite with rare bedding. S1-spaced. Calcite veining less extensive than above (5%) often with siderite/dolomite? selvages. Finely bedded after 27.0m. Minor anhydrite Xls on 090° fractures. Almost massive py (50%) fine-grained overgrown by 1-2mm allogenic cubes @ 25.60-26.06m. 2° py throughout section.	5-8		27.78	28.77		B 351	21	2.4	180	453	874

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 2 of 8

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% py	% Po	Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
27.95	44.30			Lt. grey, silicified, well- to finely-bedded pyritiferous argillite with minor zones of slump breccia and calcite veining. Rare graphitic shale partings. Signifcnt (5-8%) secondary pyrite overgrowth diss. throughout section. Pyrrhotite up to	7		39.92	41.45		B352	15	1.8	436	392	145
							41.45	42.98		B353	25	10.0	1050	116	357
							42.98	44.20		B354	<10	6.0	644	304	676
44.30	52.40			Black, massive- to well-bedded carbonaceous (graphitic) mudstone with either wispy lamenae of pyrrhotite, alternating beds of pyrrhotite and mudstone (<1cm), massive zones of py + po, or breccia (slump) composed of fragments of chert, shale or pyrite. Fragment size 1-6 cm, angular w/ matrix. ‖ 50.85-52.12 - slump bx with frags. of chert, argillite + pyrite (massive)	1		50.60	52.12		B355	395	1.5	206	1300	148
							52.12	53.35		B356	238	1.0	130	977	198
							53.35	54.92		B357	<10	0.4	71	202	46
52.40	53.23			Black, fractured, incoherent graphitic shale/phyllite											
53.23	61.20			Massive- to moderatly well-bedded lt. grey -blue chert with graphitic partings and up to 3% diss. 2° py	2		57.35	58.05		B358	<10	1.9	182	1270	73

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% PY	% PO
61.20	64.46			Black, siliceous mudstone with evidence of good 1° sedimentary features, bedding, slumping, etc., calcite veining up to 15% with qtz veining. Same as 44.30 - 52.40 except more siliceous and more py. Section contains chert interbeds and graphitic horizons	3	
64.46	92.60			Thick section of lt. grey-blue, massive to moderately-well-bedded chert with some intervals of well-bedded cherty, black shale ie 69.49 - 73.76 m Pyrite		
92.66	94.18			LOST SECTION - FAULT GOUGE?		
94.18	96.01			chert continues as described above		
96.01	99.36			Black, siliceous mudstone, finely-bedded laminae with wisps of py + po (3-4%) defining So	3	
99.36	101.49			Black, siliceous, well-bedded mudstone with beds to 2cm, often alternating sulphides + seds Py + Po = 6-10%, 2° py disseminated throughout section	5	

Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
65.84	66.34		B359	14	1.3	40	416	27
67.36	68.03		B360	<10	0.5	43	619	79
68.93	69.23		B361	<10	0.7	23	87	90
72.36	73.71		B362	<10	1.5	44	124	28
73.71	74.98		B363	<10	1.0	34	175	14
74.98	76.38		B364	<10	0.8	29	152	13
76.38	77.70		B365	<10	0.5	12	95	8
77.70	79.00		B366	<10	0.8	11	41	<1
79.00	80.30		B367	<10	1.2	21	306	39
80.30	82.45		B368	<10	1.1	18	202	51
82.45	83.71		B369	<10	1.5	13	50	<1
83.71	85.00		B370	<10	1.7	15	84	73
85.00	86.15		B371	<10	0.4	20	70	12
86.15	87.49		B372	<10	0.4	19	193	29
87.49	88.69		B373	<10	0.5	30	128	60
88.69	89.82		B374	<10	0.5	13	88	45
89.82	91.13		B375	<10	0.5	14	47	37
91.13	92.66		B376	<10	0.6	21	249	74
94.18	96.00		B377	<10	0.5	33	136	42
96.00	97.32		B378	11	1.7	96	290	113
97.32	99.06		B379	<10	1.1	62	492	183
99.06	100.43		B380	26	1.3	154	625	346
100.46	101.69		B381	51	7.5	951	2930	381
101.69	102.10		B382	113	6.8	0.31%	0.11%	0.97%
102.10	102.78		B383	84	20.0	1.32%	0.39%	0.15%
102.78	103.48		B384	155	3.4	644	65	1505
103.48	103.77		B385	51	5.2	669	64	1531
104.10	104.55		B386	92	8.7	876	476	1286

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 4 of 8

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	%Py	%Po	Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
101.49	102.11			As above with qtz stringers to 60% of volume and increase in Py+Po to 30%											
102.11	106.38*			Well-bedded to massive sulphides (80%). Most of section is po overgrown by 2° py cubes to 4mm (fine grained). Qtz late but late. Interesting textures (replacement? not related to S) - look biogenic ~~in~~ Rare, coarse grained (2mm) galena crystals in late qtz are as epigenic stringers X-cutting Po+Py, 2-3cm galena vein X-cutting massive sulphides			104.55	105.00		B387	98	5.4	126	454	2280
							105.00	105.42		B388	57	5.3	277	290	2100
							105.42	105.97		B389	86	7.7	269	992	1148
							105.97	106.50		B390	112	11.5	362	4150	1817
							106.50	107.23		B391	386	1.7	121	1290	350
106.38	109.88			Massive to thickly bedded (5-10cm) blue grey chert cut by numerous small ~~py~~ veins - All overprinted by 1% 2° py	1		107.23	107.81		B392	24	0.6	5	724	226
							107.81	108.87		B393	20	1.3	4	79	273
109.88	116.65			Black silicified pyritic mudstone and breccia - generally well bedded with some intensely silicified zones. Grades downwards to chert sandstone @ 111 m which is generally well-bedded with beds btw 3-5cm then to finely laminated mudstone @ 114.20 with wisps of pyrite and pyrite lamenae											
				Sphalerite in qtz-py veins @ 112.4, 113.15, 116.00											

* section probably 0.45 m longer due to overdrilling ∴ total section 4.72 m

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 5 of 8

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% py	% Po	Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
116.65	118.40			Coarse grained grey-blue chert sandstone and grit-stone with well developed slump structures - poorly preserved bedding Qtz - py (30%) - sphal (8%) vein btw. 118.20 - 118.86											
118.40	120.15			Severe zone of brecciation with extensive qtz stringers @ interval & of above with massive, black, carbonaceous mudstone. Sphal in qtz-py veins @ 119.0			123.30	124.65		B394	42	4.9	45	140	168
							124.65	126.12		B395	14	1.1	5	184	155
							126.12	127.34		B396	28	2.4	6	152	262
120.15	123.15			Zone of chert and sandstone overlying black massive mudstone			127.34	128.72		B397	15	1.2	5	144	130
							128.72	130.04		B398	<10	0.6	7	14	96
							130.04	131.36		B399	<10	0.7	6	32	149
							131.36	132.89		B400	<10	0.6	3	108	151
							132.89	134.42		B401	<10	0.4	8	51	106
123.15	146.81			Light grey-white-blue chert and chert bx - generally well bedded (3-10 cm beds) cut by numerous qtz veins (<2cm) which contain 5-10% pyrite. Total section overprinted with 1-2% 2° py diss.	2		134.42	135.94		B402	32	1.7	5	29	175
							135.94	137.46		B403	<10	1.3	90	74	102
							137.46	138.98		B404	<10	0.7	8	99	76
							138.98	140.51		B405	<10	0.7	11	23	57
							140.51	142.04		B406	<10	0.3	7	21	39
							142.04	143.56		B407	<10	0.4	17	134	76
1							143.56	145.08		B408	<10	0.5	14	60	64
							145.08	146.83		B409	<10	0.7	17	144	80
146.81	148.70			Light grey well-bedded sandy siltstone with fine-grained py layering as wisps + lamerae - all overprinted by 2-3% 2° py cubes to 4mm. Section grades down hole to chert @ 148.70			146.83	148.65		B410	15	3.5	40	119	260
							148.65	150.85		B411	29	1.3	110	367	86
							150.85	152.70		B412	<10	0.6	23	88	71
							152.70	154.23		B413	<10	1.3	52	232	144
							154.23	155.75		B414	<10	0.9	3	36	163
148.70	179.05			Chert and chert bx with veinlets of qtz and qtz + py			155.75	157.28		B415	<10	0.7	2	30	92
							157.28	158.80		B416	<10	0.9	14	28	169
							158.80	160.32		B417	<10	1.3	24	87	149
							160.32	161.58		B418	<10	0.9	6	31	135
							161.58	163.37		B419	<10	1.1	4	56	329
							163.37	164.90		B420	<10	1.4	1	154	124
							164.90	166.42		B421	<10	1.2	9	18	86

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 6 of 8

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py
179.05	183.90			Dark grey, strongly silicified, moderately well-bedded sandstone with 1° slump features - with overprinted qtz stockwork bx and 2% py	
1839	185.10			Well-bedded, dark grey sandy siltstone typically in beds <5cm, pyrite as replacement (porosity controlled) all overgrown by 2-3% disseminated 2° pyrite.	
185.10	187.43			Dark grey chert sandstone silicified with some stockwork bx (10-20% qtz) late stage qtz with sphalerite @ 187.00 - 187.20	
187.43	191.11			Dk. grey sandstone and gritstone with 1° bedding features and late stage (mechanical) brecciation. Up to 6% in porosity controlled sites (ie mtx of ss and mtx of bx)	4
191.11	19583			Zone of broken graphitic mudstone in qtz bx (30% qtz)	
194.0	194.46			Well-bedded (unbrecciated) zone of sandy mudstone with up to 3% secondary pyrite	3

Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
166.42	167.95		B422	<10	1.6	2	297	91
167.95	169.47		B423	<10	0.7	<1	15	122
169.47	170.99		B424	<10	0.8	3	61	152
170.99	172.52		B425	<10	1.6	19	40	115
172.52	173.58		B426	<10	1.1	<1	10	87
173.58	175.11		B427	<10	1.3	<1	87	75
175.11	176.78		B428	<10	1.1	<1	31	88
176.78	178.31		B429	<10	1.3	<1	61	148
178.31	179.83		B430	<10	1.0	<1	95	90
179.83	181.86		B431	<10	0.7	13	261	95
181.86	183.65		B432	N/A	N/A	N/A	N/A	N/A

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py	% Po	Interval From	Interval To	Core Width	Sample No.
195.83	198.12			Dk. grey silicified sandy siltstone cross-cut by 15% (by vol) qtz veins and up to 8% py in veins + disseminated + in veinlets	6					
198.12	248.41			Black, well-laminated mudstone, sandy siltstone and lesser sandstone - with beds 1-5cm and good 1° sed. structures, lots of grading - not so distal turbidites. Beds of po (up to 2cm) interbedded with seds + clasts affected by 1° slumping + lesser bx. Po composes btw 3-8% of section Typically fine-grained by some relict ...		6				
				Lots of Soft Sed Def^n						
				Section overgrown by 2-4% py, plus veinlets upto 10% more and up to 10% more as replacement.						
				Late stage py is porosity controlled and centers porameous with silicification						
				Graphitic mudstone @ 246.00-246.89						
				" " w/ qtz-bx						
				w/ py bx @ 224.0-231.34						
				w/ qtz + py bx 222.81-224.00						
				Qtz bx @ 213-213.92, 234.84-237.74						
				Py > Po above 240.79						
				Qtz-Py (+ sphalerite) veins @ 207.45, 209.00, 211.10 211.80, 213.50-214, 215.22, 243.00.						

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-1 Page 8 of 8

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py	% Po	Interval From	Interval To	Core Width	Sample No.
248.41	274.62			Black, well-bedded muddy sandstone, with interbedded siltstone + pyrrhotite. Similar to above section - but coarser grained, fewer bx + qtz veins and less silicification. Graphitic intervals at 246.00-246.89, up to 6% Po	2	5				
				At 254.00-255.87 graphitic mudstone ± 3% py with 10% qtz veining bx						
				Lots of po in this section. less, only 2% allogenic py.						
				E.O.H. 274.62						
				DIP (ACID) TESTS						

	ESTIMATED ANGLE	TRUE ANGLE
COLLAR		45°
33.5m	47°	40°
137.2m	46°	39°
274.6m	44°	36°

DROMEDARY DDH 90-1

SAMPLE NO.	FROM	TO	WIDTH	Au (ppb)	Ag (ppm)	% Pb	% Zn	% Cu	REMARKS
344301	24.38	25.15	0.77	45	3.5	0.04	0.08	0.015	
344302	21.15	26.52	1.37	46	1.7	0.02	0.57	0.017	10% Py + Po
344303	135.42	138.42	3.00	28	0.1	0.01	0.01	0.011	chert with py veins
344304	102.10	104.10	2.00	0.02*	12*	0.35	0.07	0.006	massive sulphides +.188% As
344305	104.10	106.50	2.40	0.16*	22*	0.26	0.09	0.007	massive sulphides +.235% As
344306	28.88	30.48	1.60	69	0.6	0.03	0.02	0.007	10% po + 15% py
344307	30.48	32.10	1.62	117	0.1	0.02	0.01	0.004	15% po + 8% py
344308	32.10	34.14	2.04	131	0.1	0.04	0.02	0.003	20% po + 4% py
344309	34.14	35.10	0.86	51	0.1	0.06	0.10	0.001	4% po + 1% py
344310	35.10	36.88	1.78	47	0.1	0.04	0.03	0.002	10% po + 5% py
344311	36.88	38.34	1.46	73	0.1	0.02	0.03	0.006	4% po + 1% py
344312	38.34	39.92	1.58	67	0.1	0.02	0.07	0.005	6% po + 1% py (to 44.3 m)
344313	44.30	47.00	2.70	90	1.1	0.06	1.32	0.007	2% po (bl.mudstone)
344314	49.85	50.60	0.75	220	4.8	0.27	0.17	0.016	3% po (slump bx)
344315	100.40	102.10	1.60	133	4.1	0.14	0.01	0.012	5% po + 3% py (MS hng wall)
344316	103.77	104.10	0.33	145	>100	2.98	0.49	0.011	Massive sulphides + gn
344317	61.26	62.00	0.74	90	0.1	0.01	0.10	0.012	cherty mudstone + py
344318	113.08	113.72	0.64	83	0.1	0.02	0.13	0.003	sandstone + sph +qtz
344319	115.65	116.30	0.75	98	3.0	0.01	0.93	0.013	"
344320	118.30	118.93	0.63	94	7.2	0.04	0.06	0.013	limestone + sph
344321	208.55	209.50	0.95	93	6.3	0.01	0.13	0.011	chert + sph
344322	211.00	211.90	0.90	115	0.1	0.02	0.05	0.010	silic'd mdstn + sph
344323	213.10	214.65	1.55	69	1.3	0.01	0.12	0.013	above with qtz/py veins
344324	233.65	234.39	0.74	26	0.1	0.01	0.08	0.012	black mudstone
344325	252.68	254.20	1.68	32	0.1	0.01	0.04	0.014	mudstone w/ po

* : in grams per tonne

SAMPLE REPORT

PROPERTY NAME: Dromedary Mountain

DATE: July 21, 1990

LOCATION: DDH - 1 - 90

N.T.S:

SAMPLER: G.S., J.P.J

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY PPb Au	PPM Ag	PPM Pb	PPM Zn	PPM As
B 351	27.78 to 28.77m - Med. grey siliceous siltstone with 2% to 4% Sx aggregates (up to 1mm dia.) which are comprised of fine grained py.	21	2.4	180	453	874
B 352	39.92 to 41.45m - Med. grey siliceous siltstone with 10% graphitic intercalations 5 to 15% fine grained py occurring in aggregates up to 1 mm in diameter The aggregates occur along and in the wall of fractures, and the py has a re-crystallized texture. Up to 15% v.f. fractures. - 5 to 10% q/z veinlets (up to 1mm dia) which are post Sx mineralization.	15	1.8	436	392	145
B 353	41.45 to 42.98 . as above	25	10.0	1050	116	357

SAMPLE REPORT

PROPERTY NAME: Dromedary Mtn DATE: July 21, 1990

LOCATION: DDH - 1 - 90 N.T.S:

SAMPLER: G.S., J.P.J

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY PPB Au	PPM Ag	PPM Pb	PPM Zn	PPM As
B 354	42.98 m to 44.2 m - as above	<10	6.0	644	304	676
B 355	50.60 m to 52.12 m - Dark grey, siliceous mudstone with graphitic intercalations - moderately fractured with pods (less than 1mm to 3 cm in length) of fine grained py (2% to 5%) occurring in lamella and along fractures. - trace to 2% v.f. grained red sphalerite occurs locally along later fractures (less than 1mm in width). The rock and py pods exhibit soft sediment deformation. Minor chert intercalations	395	1.5	206	1300	148
B 356	52.12 m to 53.35 m - Graphitic argillite intercalated with chert - up to 5% dissem py and occassional sphalerite along fractures which are stratabound.	238	1.0	130	977	198

SAMPLE REPORT

PROPERTY NAME: Dromedary Mtn

DATE: July 21, 1990

LOCATION: DDH - 1 - 90

N.T.S:

SAMPLER: GS. JPS.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 357	53.35 to 54.92 m - Medium grey chert moderately fractured, up to 2% v.f. py along fractures and in pods.	<10	0.4	71	202	46
B 358	57.35 to 58.05 m - Med. grey chert moderately fractured, 1% to 3% v.f. py in lamellae and along fractures.	<10	1.9	182	1270	73
B 359	65.84 to 66.34 m - Med. grey chert as above	14	1.3	40	416	27
B 360	67.36 to 68.03 m - Med. grey chert w/ minor graphitic argillite intercalations - 2% to 4% v.f. py along fractures	<10	0.5	43	619	79
B 361	68.93 to 69.23 m - as above with 5 to 15% quartz veining (< 1 mm to 1 cm wide)	<10	0.7	23	87	90

SAMPLE REPORT

PROPERTY NAME: Dromedary Mtn. DATE: July 21 1990

LOCATION: DDH-1-90 N.T.S:

SAMPLER: G.S., J.P.J.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 362	72.36 to 73.71 m - Med. grey chert with up to 10% graphitic intercalations - up to 5% v.f. fine grained pyrite occurring in aggregates (up to 1mm dia.) along lamellae.	<10	1.5	44	124	28
B 363	73.71 to 74.98 m - Med. grey chert moderately fractured, up to 5% qtz veinlets and 1% to 3% v.f. dissem py.	<10	1.0	34	175	14
B 364	74.98 to 76.38 m - Med grey chert weak to moderately fractured - locally there may be up to 5% qtz veinlets - 1% to 3% fine grained aggregates composed of v.f. py occurs along fractures and along lamellae. Locally may be up to 5% py.	<10	0.8	29	152	13
B 365	76.38 to 77.70 m - Chert (as above)	<10	0.5	12	95	8

SAMPLE REPORT

PROPERTY NAME: Dromedary Mtn. DATE: July 21 1990

LOCATION: DDH - 1 - 90 N.T.S:

SAMPLER: G.S., J.P.S.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 366	77.70 to 79.00 m - Chert (as above)	<10	0.8	11	41	<1
B 367	79.00 to 80.30 m - Chert (as above)	<10	1.2	21	306	39
B 368	80.30 to 82.45 m - Chert (as above)	<10	1.1	18	202	51
B-369	82.45 to 83.71 m - Chert (as above)	<10	1.5	13	50	<1
B-370	83.71 to 85.00 m - Chert (as above)	<10	1.7	15	84	73
B-371	85.00 to 86.15 m - Chert (as above)	<10	0.4	20	70	12
B-372	86.15 to 87.49 m - Chert (as above)	<10	0.4	19	193	29
B-373	87.49 to 88.69 m - Chert (as above)	<10	0.5	30	128	60
B-374	88.69 to 89.82 m - Chert (as above)	<10	0.5	13	88	46

AME REI T

PROPERTY NAME: Dromedary Mtn. DATE: July 21, 1990

LOCATION: DDH-1-90 N.T.S:

SAMPLER: GS, JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 375	89.82 to 91.13 m - Chert (as above)	<10	0.5	14	47	37
B 376	91.13 to 92.66 m - Chert (as above)	<10	0.6	21	249	74
B 377	94.18 to 96.00 m - Intercalated argillite, graphitic argillite and siliceous argillite - 1 to 2% v.f. py as fracture fillings	<10	0.5	33	126	42
B 378	96.00 to 97.32 m - Intercalated argillite, graphitic arg. + siliceous arg. with locally occurring quartz veinlets (5 to 10%) - Moderately fractured - 3 to 5% v.f. grained py as disseminations, fracture fillings and hosted in qtz veinlets	11	1.7	96	290	113

SAMPLE REPORT

PROPERTY NAME: Dromedary Mtn. DATE: July 21 1990

LOCATION: DDH-01-90 N.T.S:

SAMPLER: GS, JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY PPB Au	PPM Ag	PPM Pb	PPM Zn	PPM As
B 379	97.84 TO 99.06 - Siliceous argillite with 10% graphite intercalations - up to 10% qtz veinlets - moderately fractured - 5 to 15% v.f. grained pyrite occurring in aggregates of up to 1 mm diameter. - The py occurs along lamellae and some qtz veinlets. - Trace sphalerite in a qtz veinlet.	<10	1.1	62	492	183
B 380	99.06 TO 100.43 m - Siliceous argillite - weakly fractured - v.f. grained py (3 to 5%) occurring in aggregates (up to 1mm dia) occurring along lamellae. Local concentrations of 10% to 15% Sx (10% py, 5% po) occurring in stratiform lenses, pods + wisps.	26	1.3	151	625	346
B 381	100.43 TO 101.69 m - as above - local beds of massive py + po up to 1 cm thick. and 1 bed measuring 7 cm thick.	51	75	951	2930	381

AMI ___ REL ___T

PROPERTY NAME: Dromedary Mtn. DATE: July 21, 1990

LOCATION: DDH - 01 - 90 N.T.S:

SAMPLER: GS. JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY				
		ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 382	101.69 TO 102.10 m - Massive v.f. pø with 10% fine grained py and 10 to 15% qtz veins	113	6.8	0.31%	0.11%	0.97%
B 383	102.10 TO 102.78 - V.f. grained massive pø with 5% fine grained pyrite aggregates occurring as disseminations and two beds (less than 1 cm thick)	84	20.0	1.32%	0.39%	0.15%
B 384	102.78 TO 103.48 - Massive pø as above but only dissem py	155	3.4	644	65	1505
B 385	103.48 TO 103.77 - Massive pø as above	51	5.2	669	64	1531
B 386	104.10 TO 104.55 - Massive v.f. pø with 2 to 3% fine grained py in aggregates up to 4 cm diameter. occ. qtz veinlets	92	8.7	876	476	1286

AMI REPORT

PROPERTY NAME: Dromedary Mtn DATE: July 21, 1990

LOCATION: DDH - 01 - 90 N.T.S:

SAMPLER: GS. JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 387	104.55 to 105.00 m - Massive v.f. grained pO with 5% to 10% fine grained py in aggregates and pods up to 1.5 cm in length	98	5.4	126	454	2280
B 388	105.00 to 105.42 - Massive v.f. grained pO with 5 to 10% fine grained py occurring along lamellae and as disseminations.	57	5.3	277	290	2100
B 389	105.42 to 105.97 - Massive v.f. grained pO with 2 to 3% fine grained disseminated py.	86	7.7	269	992	1148
B 390	105.97 to 106.50 - Massive fine to v.f. grained py with 10% pO, 10 to 15% silica and 5% cp which mainly occurs lower portion of sample interval	112	11.5	362	4150	1817

AMF ___ REI ___T

PROPERTY NAME: Dromedary Mtn DATE: July 21, 1990

LOCATION: DDH-01-90 N.T.S:

SAMPLER: GS, JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B391	106.50 to 107.23 - Argillite with minor graphitic intercalations - 10 to 40% silica - up to 10% v.f. py along lamellae and as dissem. - trace sl with silica	386	1.7	121	1290	350
B392	107.23 to 107.81 - Light grey chert - highly fractured - 5 to 7% vf. py along fractures	24	0.6	5	724	226
B393	107.81 to 108.87 - Intercalated argillite and siliceous argillite - 10% v.f. py along lamellae and as disseminations	20	1.3	4	79	273
B394	123.30 to 124.65 - Light grey chert breccia - highly fractured - up to 5% qtz veining - 2 to 3% fine grained py along fractures & stockwork texture - Occasional euhedral coarse gypsum along fractures.	42	4.9	45	140	168

AMI RE T

PROPERTY NAME: Dromedary Mtn

DATE: July 21 1990

LOCATION: DDH-01-90

N.T.S:

SAMPLER: GS JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 395	124.65 to 126.12 - Chert brxx (as above)	14	1.1	5	184	155
B 396	126.12 to 127.34 - Chert brxx (as above)	28	2.4	6	152	262
B 397	127.34 to 128.72 - Chert brxx (as above)	15	1.2	5	144	130
B 398	128.72 to 130.04 - Chert brxx (as above)	<10	0.6	7	14	96
B 399	130.04 to 131.36 - Chert brxx (as above)	<10	0.7	6	32	149
B 400	131.36 to 132.89 - Chert brxx (as above)	<10	0.6	3	108	151
B 401	132.89 TO 134.42 - Chert brxx (as above)	<10	0.4	8	51	106
B 402	134.42 TO 135.94 Chert brxx (as above)	32	1.7	5	29	178
B 403	135.94 TO 137.46 Chert brxx (as above)	<10	1.3	90	74	102

SAM RE T

PROPERTY NAME: Dromedary Mtn

DATE: July 21, 1990

LOCATION: DDH-01-90

N.T.S:

SAMPLER: GS JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY				
		ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 404	137.46 to 138.98 Chert brxx (as above)	<10	0.7	8	99	76
B 405	138.98 to 140.51 Chert brxx (as above)	<10	0.7	11	23	57
B 406	140.51 to 142.04 Chert brxx (as above)	<10	0.3	7	21	39
B 407	142.04 to 143.56 Chert brxx (as above)	<10	0.4	17	134	76
B 408	143.56 to 145.08 Chert brxx (as above)	<10	0.5	14	60	64
B 409	145.08 to 146.83 Chert brxx (as above)	<10	0.7	17	144	80
B 410	146.83 to 148.65 Siliceous Argillite with graphitic lamellae - local qtz veinlets up to 25% - v.f dissem py (5% to 10%)	15	3.5	40	119	260

AMI REPORT

PROPERTY NAME: Dromedary Mtn. DATE: July 21, 1990

LOCATION: DDH-01-90 N.T.S:

SAMPLER: GS. J.P.J

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B-411	148.65 TO 150.85 - Light grey chert brxx @ up to 5% beige mudstone intercalations - moderate to intensly fractured - fractures (1 mm wide) are filled with dark grey silica and 2% to 3% (total rock) v.f. grained py., locally 5% to 8% py. - May have occassional graphitic lamelloe. - occasional coarse gypsum along fractures.	29	1.3	810	367	86
B-412	150.85 TO 152.70 - Chert brxx (as above)	<10	0.6	23	88	71
B 413	152.70 TO 154.23 - Chert brxx as above but with local bands (1 cm wide) of massive v.f. py., also trace sl. in a silica pod.	<10	1.3	52	232	144
B 414	154.23 TO 155.75 - Chert brxx (as above)	<10	0.9	3	36	163
B 415	155.75 TO 157.28 - Chert brxx (as above)	<10	0.7	2	30	92

AMI REPORT

PROPERTY NAME: Dromedary Mtn. DATE: July 21, 1990

LOCATION: DDH-01-90 N.T.S:

SAMPLER: GS, JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY				
		ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 416	157.28 - 158.80 - Chert brxx (as above)	<10	0.9	14	28	169
B 417	158.80 - 160.32 - Chert brxx (as above)	<10	1.3	24	87	149
B-418	160.32 - 161.58 - Chert brxx (as above)	4<10	0.9	6	31	135
B-419	161.58 - 163.37 Chert brxx (as above)	<10	1.1	4	56	329
B 420	163.37 - 164.90 Chert brxx (as above)	<10	1.4	1	154	124
B 421	164.90 - 166.42 Chert brxx (as above) coarse grained stibnite at 166.0m	<10	1.2	9	18	86
B 422	166.42 - 167.95 Chert brxx (as above)	<10	1.6	2	297	91
B 423	167.95 - 169.47 Chert brxx (as above)	<10	0.7	<1	15	122
B 424	169.47 - 170.99 Chert brxx (as above)	<10	0.8	3	61	152

AME REI F

PROPERTY NAME: Dromedary Mtn DATE: July 22, 1990

LOCATION: DDH - 01 - 90 N.T.S:

SAMPLER: GS JPJ

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 425	170.99 TO 172.52 Chert brxx (as above) trace pØ	<10	1.6	19	40	115
B 426	172.52 TO 173.58 Chert brxx (as above) trace pØ	<10	1.1	<1	10	87
B 427	173.58 TO 175.11 m Chert brxx (as above) trace to 1% pØ, and local trace fine grained sl. with silica infillings - pØ replacing py	<10	1.3	<1	87	75
B 428	175.11 TO 176.78 m Chert brxx (as above) but with ~ equal amounts of v.f. grained py and pØ for a total of 3%	<10	1.1	<1	31	88
B 429	176.78 TO 178.31 m Chert brxx (as above) (ie: sample # 411)	<10	1.3	<1	61	148
B 430	178.31 TO 179.83 m Chert brxx (as above) (ie: sample # 411)	<10	1.0	<1	95	90

AME ___ REL ___

PROPERTY NAME: Dromedary Mtn. DATE: July 22, 1990

LOCATION: DDH-01-90 N.T.S:

SAMPLER: GS, JPT

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY				
		Ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B 431	179.83 to 181.86 m - Siliceous, limy sandstone/					
	mudstone, with 5 to 10% graphite interculations	<10	0.7	13	261	95
	5 to 20% quartz veinlets (<1mm to					
	2 mm in width) - 5 to 8% v.f. py					
	and trace sl along fractures					
B-432	181.86 to 183.65 - Sil Argillite					
	breex (as above) - no sl.					

DIAMOND DRILL LOG

DDH90-2

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-2 Page 1 of 3

Property DROMEDARY	NTS 105L/15	Claim ACE 277	Elevation 2175'	Azimuth 018°	Length 159.4	Dip −55°
Coordinates L50+00W / 5+50S	Dip Tests @ 30.5m - EOH (PAGE 3)	Advance	Depth	Date Collared 19 JUNE	Date Completed 29 JUNE	
Purposes	Drilled by KLUANE	Assays by NAL	Logged by C. HART			

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py	% Po	Interval From	Interval To	Core Width	Sample No.	Au ppb	Ag ppm	Pb ppm	Zn ppm	As ppm
0	15.40			OVERBURDEN											
15.40	23.16			Chert breccia with disseminated pyrrhotite (1%) and numerous pyrite stringers forming mesh-like networks (5%). Associated quartz veining and silicification. Poor recovery (20%) therefore difficult to ascertain all lithological variations.	5	1	15.40	16.00		B 433	470	12.1	0.54%	0.52%	0.46%
							16.00	16.15		B434	245	10.1	0.37%	0.54%	0.71%
							16.15	16.76		B435	27	0.2	20	95	261
							16.76	17.37		B436	27	0.3	13	76	127
							17.37	17.98		B437	<10	0.3	15	102	153
							17.98	18.90		B438	60	0.8	84	268	174
							18.90	20.42		B439	146	0.3	67	190	226
23.16	39.45			Gritty, light grey limey bindstone (carbonate sandstone), and brecciated bindstone with some silicified intervals containing qtz veining (to 20%) in breccia zones (ie. 33.45 - 34.06) Pyrrhotite (or pyrite) occurs rarely as disseminated blebs (replacement?) or as veinlets with qtz (<1%) Poor recovery (20%) to 35.50m	1	1	20.42	21.95		B440	66	0.1	24	105	94
							21.95	23.16		B441	<10	0.2	16	183	70
							23.16	23.47		B442	30	0.2	24	233	27
							25.00	26.52		B443	34	0.5	21	83	147
							26.52	27.43		B444	<10	0.6	11	199	78
							27.43	28.50		B445	<10	0.3	9	130	44
39.45	46.80			Black well-bedded, silty mudstone rhythmites with occasional thin (1mm - 1cm) beds of pyrrhotite. Beds are contorted and convoluted by soft sediment deformation (SSD). Local graphitic partings. 2-3% pyrite (replacement?) along bedding planes + 1% py in veinlets with qtz. Vis. sphalerite @ 41.80 and 45.99	3	1									
				Some intervals of severe slumping + syn-depositional brecciation											
				Beds @ 70°-90°, increasing to 45° @ 44m - 46m											

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. 90-2

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% PY	% Po	Interval From	Interval To	Core Width	Sample No.
46.80	49.70			Gritty limey bindstone as described btwn 23.16 - 39.45 m with olistostromatic breccia in uppermost section. So - 70°, no sulphides						
49.70	62.79			Black, well-bedded, graphitic and silty mudstone with bedded pyrrhotite and pyrrhotite wisps irregular throughout section (1-3%)		3				
62.79	77.40			As above, but less graphitic and slightly more po (2-5%) Bedding @ 45°. Typically sandier and more competent than graphitic mudstones		5				
77.40	88.85			Similar to 49.70 - 62.79 with only slightly less graphite, excellent primary pyrrhotite beds, typically very fine-grained (2-4%). Good bedding structures, slump features + minor bx So @ 30°		4				
88.85	90.00			As above, but sandier with blebs + pyrite (replacement?) to 1-2%	2	3				
90.00	92.60			Graphitic interval, broken core, poor recovery						
92.60	95.40			As 62.79 - 77.40 with 1-2% pyrrhotite So @ 60°. Gradational contact with lower beds		2				

AURUM GEOLOGICAL CONSULTANTS INC. DIAMOND DRILL LOG HOLE No. _____

Interval From	Interval To	Rec'y %	RQD	DESCRIPTION	% Py	% Po	Interval From	Interval To	Core Width	Sample No.	
95.40	97.25			Light grey, well bedded sandstone with 1% sylphides. Bedding well developed but @ 45° to core axis							
97.25	104.00			Almost black, graphitic mudstone with good bedding features and very fine grained beds of pyrrhotite. S_0 - 45°							
104.00	105.90			Sandy limestone interval as prev. desc.							
105.90	107.01			As 97.25 - 104.00							
107.01	110.03			Sandy light grey mudstone with rare graphitic partings and wisps of pyrrhotite (1-2%), Very thin beds - stained S_0 - 70°		2					
110.03	129.50			Sl. graphitic, well bedded, dark silty mudstone with good SSD and beds of Po (up to 5%) and beds (repl?) of Py. beds 0.5 - 3cm	1	4					
129.50	134.35			Sandy, light-grey, fairly well-bedded siltstone							
134.35	147.00			As 110.03 - 129.50							
147.00	159.41	10		Very dark, graphitic mudstone, badly broken Very poor recovery 10%							

DIP (ACID) TESTS

DEPTH	ESTIMATED ANGLE	TRUE ANGLE
COLLAR		-55°
30.5m	BAD TEST	
159.5m	56	47°
EOH		

AMI RR I

PROPERTY NAME: Dromedary Mtn. DATE: July 22, 1990

LOCATION: DDH-02-90 N.T.S:

SAMPLER: G.S.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B-433	15.40 to 16.00 m - Light to medium grey chert boxx with "stockwork-like" texture - Moderate to high degree of stockworking - Fractures are filled with dark grey to white silica and sulphides which are comprised of 3% pø, 1% py and trace to 2% fine grained red sphalerite. - Areas of massive v.f. pø (up to 25%) - good core recovery	470	12.1	0.54%	0.52%	0.46%
B-434	16.00 to 16.15 m - Blocky core, poor recovery. - Chert brxx (as above) - trace sphalerite	245	10.1	0.37%	0.54%	0.71%
B-435	16.15 to 16.76m - Blocky core, good recovery - Chert brxx (as above) but only 1% v.f. py along fractures	27	0.2	20	95	261

AMI RE T

Pg 2 of

PROPERTY NAME: Dromedary Mtn

DATE: July 22, 1990

LOCATION: DDH-02-90

N.T.S:

SAMPLER: G.S.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B-436	16.76 to 17.37 m - Intercalated chert and sandstone with a moderate to high degree of "stockwork-like" texture - The fractures are filled with dark grey to white silica - up to 1% v.f. py along fractures	27	0.3	13	76	127
B-437	17.37 to 17.98 m - Intercalated chert and sandstone brxx (as above) - v. blocky core	<10	0.3	15	102	153
B 438	17.98 to 18.90m - V. blocky core, v poor recovery - Intercalated chert and sandstone brxx (as above)	60	0.8	84	268	174
B 439	18.90 to 20.42 m - Extremly poor recovery (ie: 1.52m over a 15 cm interval) chert brxx (as above) - only 1% v.f. py along fractures	146	0.3	67	190	226

AMEX RELEASE

PROPERTY NAME: Dromedary Mtn DATE: July 22, 1990

LOCATION: DDH-02-90 N.T.S:

SAMPLER: G.S.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B-440	20.42 to 21.95 m - Blocky core, very poor recovery - Chert brxa (as above) but only 1% v.f. py along fractures	66	0.1	24	105	94
B-441	21.95 m to 23.16 m - Core broken into small fragments v. poor recovery Intercalated chert and sandstone brxx (as above)	<10	0.2	16	183	70
B-442	23.16 to 23.47 m - Core broken into small pieces v. poor recovery - chert brxx (as above) with 1% py along fractures	30	0.2	24	233	27
B-443	25.00 to 26.52 m - Blocky core, v. poor recovery - Chert brxx (as above) with 1% py and 1% po along fractures - occassional gypsum along some fractures	34	0.5	21	83	147

MP REP

PROPERTY NAME: Dromedary Mtn DATE: July 22, 1990

LOCATION: DDH-02-90 N.T.S:

SAMPLER: G.S.

SAMPLE NUMBER	LOCATION AND DESCRIPTION	GEOCHEM/ASSAY ppb Au	ppm Ag	ppm Pb	ppm Zn	ppm As
B-444	26.52 to 27.43 m - Blocky core, extremely poor recovery - siliceous argillite with graphitic intercalations (≤ 1mm) - Moderately fractured, and filled with silica. - 1% v.f. dissem. py	<10	0.6	11	199	78
B-445	27.43 to 28.50 m - Blocky core, poor recovery - Intercalated limey argillite and siliceous argillite with graphitic lamellae. No visible Sx	<10	0.3	9	130	44
	Note: $S_0 \wedge CA$ varies from 15 to 65°, average = 35 to 45°					

DDH-90-1 Collar = L6187W, A 930S
Azimuth = 018° true
Dip = -47°





LEGEND

- Overburden
- Siliceous Argillite, may have minor graphite intercalations
- Argillite and Graphitic Argillite
- Intercalated Chert and Argillite
- Chert Breccia (Exhalite (?))
- Intercalated Sandstone, Limey Sandstone, Argillite and Graphitic Argillite
- Bedded Massive Sulphide, up to 80% pyrrhotite, 5 to 10% pyrite, 10 to 15% silica with local fracture controlled galena
- Fault

092882

DROMEDARY MOUNTAIN
DDH-90-1
SECTION 6187W (Looking West)
Scale 1:500 Date: August 1990
Compiled by: G. Shevchenko

AURUM GEOLOGICAL CONSULTANTS INC.

FIGURE #4

MAP#105L/15 Doc#092882 (243)

DDH-90-2 Collar: 5000 W 550S
Azimuth: 018°
Dip: -55°



SAMPLE #	WIDTH (m)	Au (ppb)	Ag (ppm)	Pb (ppm)	Zn (ppm)	As (ppm)
B-433	0.60	470	12.1	0.54%	0.52%	0.46%
B-434	0.15	245	10.1	0.37%	0.55%	0.71%
B-435	0.61	27	0.2	20	95	261
B-436	0.61	27	0.3	13	76	127
B-437	0.61	—	0.3	15	102	153
B-438	0.92	60	0.8	84	268	174
B-439	1.52	146	0.3	67	190	226
B-440	1.53	66	0.1	24	105	94
B-441	1.21	—	0.2	16	183	70
B-442	0.31	30	0.2	24	233	27
B-443	1.52		34	0.5	21	83
						147

LEGEND

- Overburden
- Chert (exhalite?) Breccia
- Intercalated Chert Breccia and Limey Sandstone
- Intercalated Sandstone, Limey Sandstone Argillite and Graphitic Argillite

092882

DROMEDARY MOUNTAIN
DDH-90-2
SECTION 5000 W (Looking West)
Scale = 1:500 Date: August 1990
Compiled by: G. Shevchenko

AURUM GEOLOGICAL CONSULTANTS INC. FIGURE # 5

MAP#1054/15 Doc#092882 (244)

ANALYTICAL REPORTS

Northern Analytical Laboratories ltd.

July 4,1990

Work Order # 34693

Aurum Geological Consultants Inc.
P.O. Box 5179
Whitehorse, Yukon
Y1A 4S3

File # 34693a

Project # 21

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	% Cu	% Pb	% Zn
344301	45	3.5	0.015	0.04	0.08
344302	46	1.7	0.017	0.02	0.57
344303	28	<0.1	0.011	0.01	<0.01
344304	89	0.6	0.007	0.03	0.02
344307	117	<0.1	0.004	0.02	<0.01
344308	131	<0.1	0.003	0.04	0.02
344309	51	<0.1	0.001	0.06	0.10
344310	47	<0.1	0.002	0.04	0.03
344311	73	<0.1	0.006	0.02	0.03
344312	67	<0.1	0.005	0.02	0.07
344313	90	1.1	0.007	0.06	1.32
344314	220	4.8	0.016	0.27	0.17
344315	133	4.1	0.012	0.14	0.01
344316	145	>100	0.011	2.98	0.43
344317	90	<0.1	0.012	0.01	0.10
344318	83	<0.1	0.003	0.02	0.13
344319	98	3.0	0.013	<0.01	0.33
344320	94	7.2	0.013	0.04	0.06
344321	93	6.3	0.011	0.01	0.13
344322	115	<0.1	0.010	0.02	0.05
344323	69	1.3	0.013	<0.01	0.12
344324	26	<0.1	0.012	0.01	0.08
344325	32	<0.1	0.014	0.01	0.04

Au -- 15g Fire Assay/AAS
Ag -- Aqua Regia Digestion/AAS Geochem
Metals -- Aqua Regia Digestion/AAS Assay

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, YT, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

June 26,1990

Work Order # 34684

Aurum Geological Consultants Inc.
P.O. Box 5179
Whitehorse, Yukon
Y1A 4S3

Project # 21

Assay Certificate for Samples Provided

Sample	g/t Au	g/t Ag	% Cu	% Pb	% Zn	% As
344304	0.02	12	0.006	0.352	0.070	0.188
344305	0.16	22	0.007	0.257	0.085	0.235

Au -- 10g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Assay

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, YT, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262b

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B381	51	7.5	95	951	2930	381	260
B382	113	6.8	40	4190	4040	>10000	129
B383	84	20.0	93	>10000	6900	2710	159
B384	155	3.4	84	644	65	1505	98
B385	51	5.2	84	669	64	1531	93
B386	92	8.7	90	876	476	1286	121
B387	98	5.4	111	126	454	2280	112
B388	57	5.3	89	277	290	2100	96
B389	86	7.7	107	269	992	1148	96
B390	112	11.5	58	362	4150	1817	190
B391	386	1.7	19	121	1290	350	76
B392	24	0.6	34	5	724	226	15
B393	20	1.3	54	4	79	273	24
B394	42	4.9	32	45	140	168	47
B395	14	1.1	46	5	184	155	29
B396	28	2.4	58	6	152	262	21
B397	15	1.2	50	5	144	130	19
B398	<10	0.6	53	7	14	96	24
B399	<10	0.7	59	6	32	149	44
B400	<10	0.6	51	3	108	151	48
B401	<10	0.4	41	8	51	106	53
B402	32	1.7	75	5	29	175	48
B403	<10	1.3	65	90	74	102	78
B404	<10	0.7	61	8	99	76	18
B405	<10	0.7	50	11	23	57	15
B406	<10	0.3	47	7	21	39	15
B407	<10	0.4	64	17	134	76	21
B408	<10	0.5	45	14	60	64	19
B409	<10	0.7	23	17	44	80	24
B410	15	3.5	63	40	119	260	46

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: [403] 668-4968 Fax: [403] 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262a

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B351	21	2.4	32	180	453	874	164
B352	15	1.8	12	436	392	145	33
B353	25	10.0	7	1050	116	357	44
B354	<10	6.0	30	644	304	676	290
B355	395	1.5	38	206	1300	148	75
B356	238	1.0	32	130	977	198	81
B357	<10	0.4	7	71	202	46	16
B358	<10	1.9	30	182	1270	73	78
B359	14	1.3	35	40	416	27	42
B360	<10	0.5	35	43	619	79	33
B361	<10	0.7	16	23	87	90	27
B362	<10	1.5	38	44	124	28	31
B363	<10	1.0	37	34	175	14	30
B364	<10	0.8	29	29	152	13	33
B365	<10	0.5	16	12	95	8	13
B366	<10	0.8	17	11	41	<1	3
B367	<10	1.2	16	21	306	39	3
B368	<10	1.1	23	18	202	51	6
B369	<10	1.5	19	13	50	<1	20
B370	<10	1.7	19	15	84	73	5
B371	<10	0.4	21	20	70	12	25
B372	<10	0.4	27	19	193	29	33
B373	<10	0.5	29	30	128	60	46
B374	<10	0.5	24	13	88	45	39
B375	<10	0.5	14	14	47	37	23
B376	<10	0.6	20	21	249	74	38
B377	<10	0.5	56	33	136	42	64
B378	11	1.7	69	96	290	113	81
B379	<10	1.1	53	62	492	183	91
B380	26	1.3	30	154	625	346	231

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Certified Science Technologists and Technicians of British Columbia Applied
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262c

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B411	29	1.3	48	110	367	86	33
B412	<10	0.6	51	23	88	71	16
B413	<10	1.3	109	52	232	144	49
B414	<10	0.9	40	3	36	163	19
B415	<10	0.7	29	2	30	92	28
B416	<10	0.9	44	14	28	169	34
B417	<10	1.3	49	24	87	149	45
B418	<10	0.9	86	6	31	135	50
B419	<10	1.1	92	4	56	329	37
B420	<10	1.4	73	1	154	124	26
B421	<10	1.2	59	9	18	86	115
B422	<10	1.6	64	2	297	91	49
B423	<10	0.7	49	<1	15	122	28
B424	<10	0.8	57	3	61	152	27
B425	<10	1.6	48	19	40	115	17
B426	<10	1.1	31	<1	10	87	9
B427	<10	1.3	49	<1	87	75	17
B428	<10	1.1	46	<1	31	88	11
B429	<10	1.3	37	<1	61	148	14
B430	<10	1.0	68	<1	95	90	8
B431	<10	0.7	34	13	261	95	27
B432	94	0.1	27	4	34	114	33
B433	470	12.1	57	7110	>10000	5030	109
B434	245	10.1	61	6510	>10000	>10000	81
B435	27	0.2	30	20	95	261	20
B436	27	0.3	22	13	76	127	20
B437	<10	0.3	25	15	102	153	23
B438	60	0.8	31	84	268	174	17
B439	146	0.3	45	67	190	226	18
B440	66	0.1	36	24	105	94	17

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Science Technologists and Technicians of British Columbia Registered
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262e

Project: Dromedary

Assay Certificate for Samples Provided

Sample	% Pb	% Zn	% As
B382	0.314	0.110	0.971
B383	1.320	0.390	0.156
B433	0.540	0.521	0.465
B434	0.375	0.540	0.710

Metals -- Aqua Regia Digestion/AAS Assay

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262d

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B441	<10	0.2	41	16	183	70	27
B442	30	0.2	41	24	233	27	22
B443	34	0.5	41	21	83	147	33
B444	<10	0.6	28	11	199	78	40
B445	<10	0.3	7	9	130	44	46

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

NAL Northern Analytical Laboratories ltd.

August 8,1990

Work Order # 08271

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08271

Project: Dromedary

Assay Certificate for Samples Provided

[Rechecks From WO# 08262]

Sample	oz/t Au
B355	0.003
B356	0.004
B391	0.002
B433	0.019
B434	0.013

Au -- 1AT Fire Assay/Grav

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

PLACER DOME EXPLORATION LIMITED
DATA STORAGE
OCT 10 1990
File Ref. 105L-14
File No. 22.9001

105 Copper Road, Whitehorse, YT, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262b

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B381	51	7.5	95	951	2930	381	260
B382	113	6.8	40	4190	4040	>10000	129
B383	84	20.0	93	>10000	6900	2710	159
B384	155	3.4	84	644	65	1505	98
B385	51	5.2	84	669	64	1531	93
B386	92	8.7	90	876	476	1286	121
B387	98	5.4	111	126	454	2280	112
B388	57	5.3	89	277	290	2100	96
B389	86	7.7	107	269	992	1148	96
B390	112	11.5	58	362	4150	1817	190
B391	386	1.7	19	121	1290	350	76
B392	24	0.6	34	5	724	226	15
B393	20	1.3	54	4	79	273	24
B394	42	4.9	32	45	140	168	47
B395	14	1.1	46	5	184	155	29
B396	28	2.4	58	6	152	262	21
B397	15	1.2	50	5	144	130	19
B398	<10	0.6	53	7	14	96	24
B399	<10	0.7	59	6	32	149	44
B400	<10	0.6	51	3	108	151	48
B401	<10	0.4	41	8	51	106	53
B402	32	1.7	75	5	29	175	48
B403	<10	1.3	65	90	74	102	78
B404	<10	0.7	61	8	99	76	18
B405	<10	0.7	50	11	23	57	15
B406	<10	0.3	47	7	21	39	15
B407	<10	0.4	64	17	134	76	21
B408	<10	0.5	45	14	60	64	19
B409	<10	0.7	23	17	44	80	24
B410	15	3.5	63	40	119	260	46

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Science Technologists and Technicians of British Columbia Applied
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262a

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B351	21	2.4	32	180	453	874	164
B352	15	1.8	12	436	392	145	33
B353	25	10.0	7	1050	116	357	44
B354	<10	6.0	30	644	304	676	290
B355	395	1.5	38	206	1300	148	75
B356	238	1.0	32	130	977	198	81
B357	<10	0.4	7	71	202	46	16
B358	<10	1.9	30	182	1270	73	78
B359	14	1.3	35	40	416	27	42
B360	<10	0.5	35	43	619	79	33
B361	<10	0.7	16	23	87	90	27
B362	<10	1.5	38	44	124	28	31
B363	<10	1.0	37	34	175	14	30
B364	<10	0.8	29	29	152	13	33
B365	<10	0.5	16	12	95	8	13
B366	<10	0.8	17	11	41	<1	3
B367	<10	1.2	16	21	306	39	3
B368	<10	1.1	23	18	202	51	6
B369	<10	1.5	19	13	50	<1	20
B370	<10	1.7	19	15	84	73	5
B371	<10	0.4	21	20	70	12	25
B372	<10	0.4	27	19	193	29	33
B373	<10	0.5	29	30	128	60	46
B374	<10	0.5	24	13	88	45	39
B375	<10	0.5	14	14	47	37	23
B376	<10	0.6	20	21	249	74	38
B377	<10	0.5	56	33	136	42	64
B378	11	1.7	69	96	290	113	81
B379	<10	1.1	53	62	492	183	91
B380	26	1.3	30	154	625	346	231

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Certified Science Technologists and Technicians of British Columbia Applied
6892
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262c

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B411	29	1.3	48	110	367	86	33
B412	<10	0.6	51	23	88	71	16
B413	<10	1.3	109	52	232	144	49
B414	<10	0.9	40	3	36	163	19
B415	<10	0.7	29	2	30	92	28
B416	<10	0.9	44	14	28	169	34
B417	<10	1.3	49	24	87	149	45
B418	<10	0.9	86	6	31	135	50
B419	<10	1.1	92	4	56	329	37
B420	<10	1.4	73	1	154	124	26
B421	<10	1.2	59	9	18	86	115
B422	<10	1.6	64	2	297	91	49
B423	<10	0.7	49	<1	15	122	28
B424	<10	0.8	57	3	61	152	27
B425	<10	1.6	48	19	40	115	17
B426	<10	1.1	31	<1	10	87	9
B427	<10	1.3	49	<1	87	75	17
B428	<10	1.1	46	<1	31	88	11
B429	<10	1.3	37	<1	61	148	14
B430	<10	1.0	68	<1	95	90	8
B431	<10	0.7	34	13	261	95	27
B432	94	0.1	27	4	34	114	33
B433	470	12.1	57	7110	>10000	5030	109
B434	245	10.1	61	6510	>10000	>10000	81
B435	27	0.2	30	20	95	261	20
B436	27	0.3	22	13	76	127	20
B437	<10	0.3	25	15	102	153	23
B438	60	0.8	31	84	268	174	17
B439	146	0.3	45	67	190	226	18
B440	66	0.1	36	24	105	94	17

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Member of Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262e

Project: Dromedary

Assay Certificate for Samples Provided

Sample	% Pb	% Zn	% As
B382	0.314	0.110	0.971
B383	1.320	0.390	0.156
B433	0.540	0.521	0.465
B434	0.375	0.540	0.710

Metals -- Aqua Regia Digestion/AAS Assay

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

July 31,1990

Work Order # 08262

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08262d

Project: Dromedary

Assay Certificate for Samples Provided

Sample	ppb Au	ppm Ag	ppm Cu	ppm Pb	ppm Zn	ppm As	ppm Sb
B441	<10	0.2	41	16	183	70	27
B442	30	0.2	41	24	233	27	22
B443	34	0.5	41	21	83	147	33
B444	<10	0.6	28	11	199	78	40
B445	<10	0.3	7	9	130	44	46

Au -- 15g Fire Assay/AAS
Metals -- Aqua Regia Digestion/AAS Geochem

RECEIVED
JUL 31 1990

Registered Professional Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

105 Copper Road, Whitehorse, TY, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

Northern Analytical Laboratories ltd.

August 8,1990

Work Order # 08271

Placer Dome Exploration Limited
103 Platinum Road
Whitehorse, Yukon
Y1A 5M3

File # 08271

Project: Dromedary

Assay Certificate for Samples Provided

[Rechecks From WO# 08262]

Sample	oz/t Au
B355	0.003
B356	0.004
B391	0.002
B433	0.019
B434	0.013

Au -- 1AT Fire Assay/Grav

Applied Science Technologists and Technicians of British Columbia
6992
GERALD F. HAYES
A.Sc.T.

PLACER DOME EXPLORATION LIMITED
DATA STORAGE
OCT 10 1990
File Ref. 105L-14
File No. 2119.001

105 Copper Road, Whitehorse, YT, Y1A 2Z7 Ph: (403) 668-4968 Fax: (403) 668-4890

STATEMENT OF COSTS

STATEMENT OF COSTS

Assessment work Valuation: Dromedary Project, NTS 105L/15, (Ace & Nora claim group)

A. Professional Services

Aurum Geological Consultants Inc.:	$20,762.50

B: Contract Services

Kluane Drilling Ltd.:	62,682.33
Trans North Air Ltd.:	49,261.95
Aerokon Aviation:	13,164.77

C: Expenses

Camp supplies, aviation fuel, analytical, etc.:	21,900.40

TOTAL VALUE OF 1990 ASSESSMENT WORK	**$167,771.95**

STATEMENT OF QUALIFICATIONS

STATEMENT OF QUALIFICATIONS

I, ROGER W. HULSTEIN, hereby certify that:

1. I am a geologist with AURUM GEOLOGICAL CONSULTANTS INC., 412-675 West Hastings Street, Vancouver, British Columbia.

2. I am a graduate of Saint Mary's University, Halifax, with a degree in geology (B.Sc., 1981) and have been involved in geology and mineral exploration continuously since 1978.

3. I am a fellow of the Geological Association of Canada (F3572).

4. I have no direct or indirect interest in the properties of Dromedary Exploration Company Ltd.

5. I am the author of this report on the Dromedary Project, Whitehorse Mining District, Yukon, which is based on my personal examination of the ground during the period May - September, 1989 and on referenced sources.

October 22, 1990

Roger Hulstein, B.Sc., FGAC