Dublin Gulch property
Diamond Drilling and Geochemical
Assessment Report 2005

NTS 106 D/4

64° 01' 56" N
135° 47' 51" W

Mayo Mining District

CLAIMS


Bob 1-9 claims
Dave 1 – 31 claims
DG 43-55, 82, 83, 85, 100-103 claims
Fiji 1-6 claims
Jeff 17, 18, 33, 34, 113-115, 117, 118, 120 claims
Mar 1-31, 33-40 claims
Mary 1-8 claims
R&D 1-8, 10, 12, 14-16 claims
Roni 1-14 claims
Smoky 1-10, 23-30, 37-41, 44-49, 51-54, 56, 58, 62-71, 74-78, 80, 83-35, 91-100, 107-109 claims
West 167-172, 174, 182, 184 claims
Dub 1-1582 claims

Report prepared by D. Hladky

Field work performed from May 7 to September 2005

StrataGold Corporation
#701, 475 Howe Street
Vancouver, BC, Canada
V6C 2B3

094876



DUBLIN GULCH, ASSESSMENT REPORT 2005

Title: 2005 Dublin Gulch Exploration Program
LQ00090

Location: Mayo Mining District, Yukon, approximately 75 kilometers northeast of Mayo and 370 kilometers due north of Whitehorse

Dates of Work: January 1st - December 31st, 2005 (Project Planning, Management and Assessment)
May 7th - September 19th, 2005 (Drilling and Regional Program)

Prepared by: D Hladky B.Sc., P.Geol., Senior Project Geologist,
StrataGold Corporation (Canada) Ltd.

Supervised by: Jim Sparling, MBA, B.Sc., P.Geol., Exploration Manager
StrataGold Corporation (Canada) Ltd.

TABLE OF CONTENTS

094876

ITEM		PAGE
1.	INTRODUCTION AND LOCATION	1
	a. Figure 1: Location Map of Dublin Gulch Claims	2
	b. Figure 2: Dublin Gulch Claims Compilation Map	3
2.	GENERAL INFORMATION	4
3.	DESCRIPTION OF WORK - DIAMOND DRILLING	4
	a. Table 2: Dublin Gulch List of 2005 Diamond Drill Holes	5
4.	METHODS OF ANALYSIS AND DATA PRESENTATION - DIAMOND DRILLING	6
5.	DESCRIPTION OF WORK - REGIONAL GEOCHEMICAL SAMPLING PROGRAM	8
6.	METHODS OF ANALYSIS AND DATA PRESENTATION - REGIONAL GEOCHEMICAL SAMPLING PROGRAM	9
7.	STATEMENT OF EXPENDITURES	
	a. Table 3: Dublin Gulch Claims Statement of Expenditures	10
8.	RECOMMENDATIONS	11
9.	STATEMENT OF QUALIFICATIONS	12

Appendix A - Dublin Gulch Claims Compilation Map
Appendix B - Dublin Gulch List of Claims for Assessment
Appendix C - Figure 3: Dublin Gulch Drill Collar Plan Map
Appendix D - Dublin Gulch 2005 Return Sample Details and ALS Chemex Assay Certificates
Appendix E - Dublin Gulch 2005 Drill Sections
Drawing 1: Dublin Gulch Section 458450 E (Hist Nad 27) DG05-292C and DG05-293C
Drawing 2: Dublin Gulch Drill Hole DG05-294C (459050 E,7100740 N)(Hist Nad 27) Looking SE at 120 deg.
Drawing 3: Dublin Gulch Section 459075 E (Hist Nad 27) DG05-280C, DG05-282C, DG05284C, DG05-288C and DG05-290C with Historic Drill Holes
Drawing 4: Dublin Gulch Section 459125 E (Hist Nad 27) STEINER ZONE DG05-296C with Historic Drill Holes
Drawing 5: Dublin Gulch Section 459175 E (Hist Nad 27) DG05-286C
Drawing 6: Dublin Gulch Section 459275 E (Hist Nad 27) DG05-298C with Historic Drill Holes
Drawing 7: Dublin Gulch Section 459475 E (Hist Nad 27) DG05-291C
Drawing 8: Dublin Gulch Section 459525 E (Hist Nad 27) DG05-289C and DG05-300C
Drawing 9: Dublin Gulch Section 459575 E (Hist Nad 27) DG05-287C and DG05-297C with Historic Drill Holes

Drawing 10: Dublin Gulch Section 459600 E (Hist Nad 27)
DG05-281C with Historic Drill Holes
Drawing 11: Dublin Gulch Section 459625 E (Hist Nad 27)
DG05-299C and DG05-301C
with Historic Drill Holes
Drawing 12: Dublin Gulch Section 459675 E (Hist Nad 27)
DG05-278C, 279C and 283C
with Historic Drill Holes
Drawing 13: Dublin Gulch Section 459725 E (Hist Nad 27)
DG05-276C, 277C, 285C and 295C
with Historic Drill Holes
Drawing 14: Dublin Gulch Section 459775 E (Hist Nad 27)
DG05-309C with Historic Drill Holes
Drawing 15: Dublin Gulch Section 459875 E (Hist Nad 27)
DG05-305C with Historic Drill Holes
Drawing 16: Dublin Gulch Section 459925 E (Hist Nad 27)
DG05-303C, 306C, 307C and 308C
with Historic Drill Holes
Drawing 17: Dublin Gulch Section 460025 E (Hist Nad 27)
DG05-302C and DG05-304C
with Historic Drill Holes

Appendix F - Dublin Gulch 2005 Diamond Drill Logs
Appendix G - ALS Chemex Assay Certificates - Drilling
Appendix H - Assay Certificates - Drilling QAQC
Includes Assay Certificates from:
- ACME Analytical
- ALS Chemex
- SGS Labs

Appendix I - Report: Review of the Dublin Gulch Quality Control Program, By Lynda Bloom of Analytical Solutions
Appendix J - Report: Report on Results of a Laboratory Audit of ALS Chemex Laboratory, North Vancouver, B.C., By Stephen Cook, Consulting Geochemist
Appendix K - Dublin Gulch Map with Regional Silt and Rock Sample Locations
Appendix L - List of Geochemical Rock Samples
Appendix M - ALS Chemex Assay Certificates - Rock Samples
Appendix N - List of Geochemical Silt Samples
Appendix O - ALS Chemex Assay Certificates - Silt Samples

1. INTRODUCTION AND LOCATION

The Dublin Gulch dispositions are located in the Mayo Mining District, Yukon Territory, approximately 75 kilometers northeast of Mayo and 370 kilometres due north of Whitehorse. The property outlined for assessment comprises 1856 contiguous quartz mining claims covering approximately 339.04 square kilometers of land.

The registered owner of the Len 1-32 and Jan 1-4 fractional claims is Janet Dickson, while the remaining claims are registered to StrataGold Corporation. The Len and Jan claims are subject to an option agreement wherein StrataGold may earn a 100% interest.

This report summarizes the Diamond Drilling activities and Regional Geochemical Sampling Program successfully completed in 2005.

A list of the Dublin Gulch Claims for Assessment is included in Appendix B of this report.




Figure 1: Dublin Gulch Claims Location Map




Figure 2: Dublin Gulch Claims Compilation Map (see Appendix A)

2. GENERAL INFORMATION

The Dublin Gulch Claims group for 2005 assessment consists of 1856 claims comprising a total of 399.04 square kilometers. Planning of the program began January 1st, 2005. The drill program was managed from May 7th to September 19th, 2005, when a total of 34 diamond drill holes were drilled. In the later part of this period a Regional Geochemical Exploration program concluded with 2418 stream sediment and 534 rock samples on the Dublin Gulch Property. Following this, assessment of the data continued through to December 31st, 2005, including a report on the Quality Control Program (Appendix I), as well as an ALS Chemex Laboratory Lab Audit (Appendix J). Appendices D through F contain Dublin Gulch Diamond Drill Sections and Logs, and Appendices K through O contain Rock and Silt Sample program details.

3. DESCRIPTION OF WORK – DIAMOND DRILLING

During the period May 7th to September 19th, 2005, 34 Diamond Drill holes were drilled on the Dublin Gulch claims. Two drills and a D6 Cat, owned by Britton Brothers Ltd., were contracted by StrataGold Corporation to complete the drill program intended to upgrade previous resource estimates, and explore new targets on the property. Where available, historical roads and pads were used, though commonly new access roads and drill pads were created to accommodate drilling. All drill holes were drilled for HQ size core, though occasionally the hole was reduced to NQ size core due to drilling complications. The core was drilled in 5 foot lengths and at shift change, transported down to the Dublin Gulch camp, located near the confluence of Dublin Gulch creek and Haggart Creek. Here the core was logged and split using two Diamond Bladed Saws, and sealed in plastic sample bags along with the sample tag. An extensive routine of Quality Assurance and Control (QA/QC) procedures were followed during sampling and subsequent assaying. These procedures are outlined in the following section.

Table 2: Dublin Gulch List of 2005 Diamond Drill Holes

DRILL HOLE	Drill	Real Easting UTM NAD 27	Real Northing UTM NAD 27	New Easting UTM NAD 83	New Northing UTM NAD 83	New Easting NAD 27 (Hist Grid -30m)	New Northing NAD 27 (Hist Grid +10m)	Elev	Depth (m)	Az	Dip	Start Date	End Date
DG05-276C	38-1	459725	7099241	459625.84	7099419.68	459714.28	7099244.47	1031.82	258.15	0	-50	21/05/05	26/05/05
DG05-277C	38-1	459734	7099317	459634.61	7099496.26	459723.06	7099321.05	1049.90	198.12	0	-50	27/05/05	31/05/05
DG05-278C	38-1	459695	7099330	459596.15	7099508.46	459684.59	7099333.25	1036.66	179.82	0	-50	01/06/05	04/06/05
DG05-279C	38-1	459686	7099269	459587.18	7099447.38	459675.62	7099272.16	1024.94	201.16	0	-50	04/06/05	08/05/05
DG05-280C	38-2	459090	7099144	458990.72	7099323.03	459079.16	7099147.83	898.34	206.64	0	-50	06/05/05	10/05/05
DG05-281C	38-1	459612	7099246	459512.62	7099424.31	459601.06	7099249.10	996.37	222.49	0	-50	08/06/05	12/06/05
DG05-282C	38-2	459086	7099243	458986.50	7099422.21	459074.94	7099247.01	887.87	251.46	0	-50	10/05/05	15/05/05
DG05-283C	38-1	459686	7099091	459587.05	7099269.40	459675.49	7099094.18	1000.26	205.73	0	-50	12/06/05	15/06/05
DG05-284C	38-2	459087	7099393	458987.93	7099571.33	459076.37	7099396.13	865.14	138.68	0	-50	15/06/05	17/06/05
DG05-285C	38-1	459735	7099047	459635.83	7099225.54	459724.27	7099050.32	1029.78	192.01	0	-50	16/06/05	19/06/05
DG05-286C	38-2	459192	7099293	459093.17	7099471.56	459181.61	7099296.36	894.53	149.34	0	-50	17/06/05	20/06/05
DG05-287C	38-1	459589	7099202	459490.04	7099380.90	459578.48	7099205.69	973.93	219.46	0	-50	19/06/05	22/06/05
DG05-288C	38-2	459094	7099046	458994.60	7099225.19	459083.04	7099049.99	909.11	195.37	0	-50	20/06/05	22/06/05
DG05-289C	38-1	459536	7099252	459437.24	7099430.43	459525.68	7099255.22	964.82	207.25	0	-60	22/06/05	24/06/05
DG05-290C	38-2	459094	7099046	458994.60	7099225.19	459083.04	7099049.99	909.11	196.90	180	-50	23/06/05	26/06/05
DG05-291C	38-1	459488	7099249	459389.33	7099427.36	459477.77	7099252.15	935.83	266.70	0	-55	25/06/05	15/07/05
DG05-292C	38-2	458469	7098570	458369.92	7098749.10	458458.35	7098573.91	752.27	202.68	0	-50	08/07/05	10/07/05
DG05-293C	38-2	458438	7098457	458338.89	7098635.60	458427.32	7098460.41	757.20	166.11	0	-50	11/07/05	14/07/05
DG05-294C	38-2	459060	7100737	459080.00	7100730.00	459050.00	7100740.00	833.00	268.21	30	-50	15/07/05	18/07/05
DG05-295C	38-1	459738	7099158	459639.03	7099336.87	459727.47	7099161.66	1015.92	281.94	0	-50	15/07/05	20/07/05
DG05-296C	38-2	459136	7099847	459036.47	7100025.94	459124.92	7099850.75	919.47	198.11	0	-50	19/07/05	21/07/05
DG05-297C	38-1	459587	7099301	459488.31	7099480.29	459576.76	7099305.08	994.80	265.16	0	-60	21/07/05	26/07/05
DG05-298C	38-2	459284	7099384	459185.09	7099562.47	459273.53	7099387.26	891.71	280.40	0	-65	21/07/05	26/07/05
DG05-299C	38-1	459639	7099325	459540.22	7099504.07	459628.66	7099328.86	1014.92	294.13	0	-55	26/07/05	30/07/05
DG05-300C	38-2	459540	7099193	459441.04	7099371.31	459529.48	7099196.10	950.55	246.89	0	-50	27/07/05	31/07/05
DG05-301C	38-1	459639	7099198	459540.29	7099377.17	459628.73	7099201.96	993.44	307.83	0	-50	31/07/05	05/08/05
DG05-302C	38-2	460036	7099272	459936.69	7099450.96	460025.14	7099275.74	1179.01	306.92	0	-50	01/08/05	05/08/05
DG05-303C	38-1	459938	7099273	459839.20	7099451.36	459927.64	7099276.14	1134.64	292.59	0	-50	05/08/05	10/08/05
DG05-304C	38-2	460037	7099200	459937.68	7099378.55	460026.13	7099203.34	1168.32	309.36	0	-50	05/08/05	10/08/05
DG05-305C	38-2	459888.3	7099589.2	459789.19	7099767.98	459877.63	7099592.78	1106.42	259.07	180	-55	10/08/05	15/08/05
DG05-306C	38-1	459936	7099203	459836.78	7099381.72	459925.22	7099206.50	1116.61	271.25	0	-50	10/08/05	16/08/05
DG05-307C	38-1	459936	7099142	459836.91	7099320.95	459925.35	7099145.73	1111.25	291.07	0	-50	17/08/05	23/08/05
DG05-308C	38-1	459936	7099093	459837.21	7099272.10	459925.65	7099096.88	1117.21	299.30	0	-50	24/08/05	01/09/05
DG05-309C	38-1	459789	7099249	459689.44	7099428.17	459777.88	7099252.96	1067.54	274.61	0	-50	01/09/05	08/09/05
TOTAL									8104.93				

Initially, return samples, or silt taken from the return mud while drilling, were collected at the drill every 5 feet (~1.53m) from the bottom of the casing to the depth that return was lost down the whole. In some cases, return was lost after only a few samples, in other cases, return lasted for the majority of the hole. The return samples were collected in large porous bags that allowed the water to slowly pass through or dry, while retaining the fine grained sample. These bags were then arranged in series and assigned a sample number. No Quality Control samples were included with the Return Samples. Return samples were collected for Holes DG05-276C to DG05-277C, and DG05-280C through DG05-284C. This exercise was stopped after Hole DG05-284C. A list of return samples is included in Appendix D, followed by the received assay certificates.

All Samples were shipped to ALS Chemex in Vancouver for analysis. Upon completion of a drill hole, collar coordinates were obtained using a Garmin GPS device, and a tripod with collar details was erected over the location.

4. METHODS OF ANALYSIS AND DATA PRESENTATION - DIAMOND DRILLING

Drill core was logged on site in the Dublin Gulch Camp, with sample tags placed by the logging geologist at the start of each sample interval. The core was then split using a Diamond Bladed Saw, with one half of the core remaining in the box and the other half being secured in plastic sample bags. The remaining core boxes were then cross-stacked and covered in the core storage area. The core samples for analysis were then sent via land to ALS Chemex in Vancouver for analysis. A total of 7263 core samples were submitted from the field, to be analyzed for Gold by Fire Assay, with 27 element ICP. The sample procedures are detailed below.

A map showing the highlighted locations of 2005 drill holes is in Appendix C, accompanied by 16 east-looking Gold assay and lithology cross sections in Appendix E.

Strict Quality Assurance and Control (QA/QC) protocols were maintained throughout the sampling process. The routine practice for a series of 20 samples is outlined in the following table.

Table 2: QAQC Sampling Procedures (as outlined in report by Stephen Cook)

Sample		Sample	
1	Field Duplicate 1	11	
2	Field Duplicate 2	12	
3		13	
4		14	
5		15	
6		16	Blank
7		17	
8		18	
	Preparation		
9	Duplicate/Check Assay	19	
10	Standard	20	

The Field Duplicate consisted of one quarter sample. In this case, "Sample 1" was split into two halves, and then one of these halves was quartered to create "Field Duplicate 1" & "Field Duplicate 2", and the other half of "Sample 1" was placed back in the box.

The Preparation Duplicate and Check Assays were prepared during milling in the ALS Chemex lab. The number 8 sample was crushed and sieved to 70 % passing 2mm mesh. From this sample, two 250 gram portions were measured out, with one of these being sent to ACME Analytical for processing as the Check Assay. The 250 gram sample remaining at ALS Chemex was then ring-milled to 85% passing 75 micron or better. From this sample, two 30 gram samples were measured out for testing. The first was tested for both Gold by Fire Assay as well as 27 element ICP by acid digestion, and the second only for Gold by Fire Assay.

Standards were also used by StrataGold to monitor analytical accuracy. A total of 7 different Standards were incorporated into the sampling protocol. Two of the Standards were obtained from the Canadian Certified Reference Materials Project (CANMET), and were measured out with an electric scale into 30.5 gram portions, double bagged in two plastic sample bags, and placed in the sample series to occur approximately once every 100 samples. The other five standards (OREAS Standards) were obtained as pre-measured 60 gram pouches from Analytical Solutions Ltd. One of these was chosen by the core logging geologist to occur in each of the remaining 4 out of 100 standard samples.

The Blank sample used consisted of barren Dolomite purchased in 30 lb bags. Approximately 1.5 to 2 kilograms of dolomite were placed in a plastic bag and submitted once every 20 samples. 12 samples, including one standard sample, were sent to each of 3 labs to test the consistency as a blank sample and to verify that no gold was

present. The results from these tests are included in the Drilling QAQC section in Appendix H.

The samples, once received by ALS Chemex, underwent the following procedure:

- The received sample was weighed and dried if necessary
- The sample was then crushed to 70% of the sample passing <2mm
- The sample was split using a riffle splitter
- The sample was then pulverized to 85% passing <75 um, with the crushers and pulverizers being washed at the beginning and end of the sample batch, and at the beginning of the technicians shift
- Followed by 30 gram Fire Assay and AAS with trace Hg via cold vapor/AAS
- Finally 27 element four acid ICP-AES

The analytical results were placed in an Access database as they were received. The original assay certificates received from ALS Chemex for the Drill Core and QAQC samples as well as the certificates from ACME Analytical Ltd. for the Check Assay samples, are presented in Appendix G for Drilling, and Appendix H for Drilling QAQC.

Due to the need to have the initial data reviewed, results from DG05-276C to DG05-302C were sent to Lynda Bloom of Analytical Solutions Ltd. for a review of the quality control program at Dublin Gulch. Based on the suggestions of this report, 373 samples were resubmitted to evaluate the consistency of the results of some of the original QAQC samples. It was also suggested to test the sampling procedures at ALS Chemex. For this, 10 samples with a variety of Au and Bi values, were submitted. For these, the remaining coarse fraction from the original sample was crushed such that the entire sample passed through a 2mm mesh. The sample was then riffle split into as many 500 gram portions as possible. Each of these samples was then pulverized, and from these new pulps three 50 gram samples were taken and analyzed for gold by Fire Assay.

The report received from Lynda Bloom is included in Appendix I. A lab audit of the ALS Chemex Ltd. North Vancouver lab was carried out by Stephen Cook on October 27th, 2005 and the report is included in Appendix J.

5. DESCRIPTION OF WORK - REGIONAL GEOCHEMICAL SAMPLING PROGRAM

The Regional Geochemical Exploration program consisted of a helicopter supported Stream Sediment (Silt) and Rock Sampling Program over much of the claim block. 2418 Stream sediment (silt) samples were collected at approximately 100 meter spacing along

current and seasonal drainages. 534 Rock samples were taken of quartz veins and mineralization in outcrop or sub-crop. Sample locations were flagged, with samples placed in stream sediment bags or plastic bags with sample tags, and shipped to ALS Chemex in Vancouver.

6. METHOD OF ANALYSIS AND DATA PRESENTATION – REGIONAL GEOCHEMICAL SAMPLING PROGRAM

Regional Samples, once collected, were sorted and placed into rice bags. Approximately 1 in 20 samples was a sample standard, the same as used for drill core sample quality control. In addition, approximately 1 in 20 samples was a sample duplicate, where the original and the following sample in the series were taken from the sample location. **Both the Rock and Stream Sediment (Silt) samples were processed the same as the Diamond Drilling core samples. For a list of the analytical procedures, refer to above.**

A map showing both the rock and silt sample locations is included in APPENDIX K. The list of Rock Samples is included in Appendix L with the ALS Assay Certificates included in Appendix M. The list of Stream Sediment (Silt) Samples is included in Appendix N, with the ALS Assay Certificates included in Appendix O.

7. STATEMENT OF EXPENDITURES


Table 2: Dublin Gulch Project Statement of Expenditures

	Through to 31/12/05
Accommodation and Meals	$79,464.53
Assays Geochem Analysis	$278,679.81
Camp Expense	$1,220.00
Helicopter	$96,671.85
Communication /Telephone	$22,267.23
Bulldoze & Equipment Contract	$202,257.69
DD Bulld & Equipment Contract	$22,520.00
Drilling	$757,375.42
DD Contractor - Direct	$40,762.20
DD Contractors Mob/Dem	$15,000.00
Drill Supplies	$72,389.00
Equipment Maintenance	$12,646.51
Equipment Rentals	$63,089.38
Expediting	$12,522.34
Fuel	$9,480.83
Fuel - Unleaded/100LL	$41.14
Fuel - Propane	$3,139.90
Fuel - Jet B	$13,696.03
Fuel - Diesel	$83,588.39
General Consultant	$46,223.99
Geophysical Consultants	$35,459.59
Geological Consultants	$475,706.49
Cook/First Aid Attendant	$51,088.31
Contract Labour	$276,740.24
Materials & Supplies	$249,755.68
Printing & Reproduction	$23,028.99
Truck Rental	$42,321.95
Delivery/Shipping	$73,277.26
Travel & Freight	$1,333.68
Travel Costs	$40,867.81
Worker's Compensation	$10,538.77
Warehouse	$14,639.16
Safety Supplies	$13,752.23
Totals	**$3,141,546.40**

8. RECOMMENDATIONS

It is recommended that the Dublin Gulch mineral dispositions described within this assessment report be held pending further geological and geochemical review, including the evaluation of the 43-101 report and updated resource estimate compiled by Wardrop Engineering Inc.

Respectfully submitted,



Jim Sparling, MBA, B.Sc., P.Geo.

Exploration Manager - StrataGold Corporation

7.0 CERTIFICATE OF QUALIFICATIONS

1. I **Jim Sparling**, of 839 Old Lillooet Rd, North Vancouver, British Columbia, Canada, hereby state - that I am the Exploration Manager with StrataGold Corporation, with offices at 701 Howe Street, Vancouver, British Columbia, V6C 2B3, and that:

2. I hold a BA (Economics Major) from the University of Manitoba, Winnipeg, Manitoba (1978), a B.Sc. (Advanced Geology) from the University of Saskatchewan, Saskatoon, Saskatchewan (1984) and an MBA from Royal Roads University, Victoria, British Columbia (2003).

3. I have 19 years experience with various mining and oil and gas companies in Canada. My primary employment since 1992 has been in the field of mineral exploration.

2004	Exploration Manager, North and Central America, StrataGold Corporation
2003	Project Geologist, StrataGold Corporation
1994 - 2003	Project Geologist and Geophysical Crew Chief Hudson Bay Exploration & Development Co. Ltd.
1992 - 1994	Geophysical Crew Chief/ Technician, Brad Koop Exploration Ltd.
1989 - 1992	Geological Systems and Data Base Analyst, Petro Canada Resources Ltd.
1988 - 1989	Geological Consultant, Schindler Exploration, Indian and Northern Affairs (Minerals West)
1987 - 1988	Field Exploration Geologist, Hudson Bay Exploration & Development Co. Ltd.
1985 - 1987	Wellsite Geologist, Geotemp Consulting Ltd.
1984 - 1985	Field Exploration Geologist, Hudson Bay Exploration & Development Co. Ltd.

4. I am a practicing member in good standing with the Association of Professional Engineers and Geoscientists of Manitoba and Saskatchewan.

5. I have extensive exploration and development project experience with volcanic massive sulphide ore deposit geology and hydrothermal alteration, and experience with gold ore deposit geology. This experience has allowed me to become familiar with the evaluation of both regional and property geology, prospecting, geophysical surveys, diamond core drilling, underground exploration, development and production, and permitting processes


geophysical surveys, diamond core drilling, underground exploration, development and production, and permitting processes in Manitoba, Saskatchewan, Nunavut Territory and the Yukon Territory.

6. This report is based upon data collected during the 2005 Diamond Drilling and Geochemical sampling program in The Yukon Territory, Canada in 2004.

Dated at Vancouver, British Columbia; Friday, February 10, 2006

Respectfully submitted,

Jim Sparling



Jim Sparling, MBA, B.Sc., P.Geo.

Exploration Manager - StrataGold Corporation

APPENDIX A

Dublin Gulch Claims Map for Assessment

094876

StrataGold Corporation

Date:	2/12/2025
Author:	DH
Check:	Vancouver
Figure:	2
Scale:	1:2500

DUBLIN GULCH
Claims Compilation Map

Projection: UTM Zone 8 (NAD 27) for Clinton

0 500 1000
metres

7592500 mN
7592000 mN
7591500 mN
7591000 mN
7590500 mN
7590000 mN
7589500 mN
7589000 mN
7588500 mN
7588000 mN
7587500 mN
7587000 mN
7586500 mN
7586000 mN
7585500 mN
7585000 mN
7584500 mN
7584000 mN
7583500 mN
7583000 mN

094876

APPENDIX B

StrataGold Dublin Gulch List of Claims for Assessment

Claim Label	Grant #	Current Expiry Date
Bob 1	YA17729	10/01/2005
Bob 2	YA17730	10/01/2005
Bob 3	YA17731	10/01/2005
Bob 4	YA17732	10/01/2005
Bob 5	YA17733	10/01/2005
Bob 6	YA17734	10/01/2005
Bob 7	YA17735	10/01/2005
Bob 8	YA17780	10/01/2005
Bob 9	YA43014	10/01/2005
Dave 1	YA17802	10/01/2005
Dave 2	YA17803	10/01/2005
Dave 3	YA17804	10/01/2005
Dave 4	YA17805	10/01/2005
Dave 5	YA17806	10/01/2005
Dave 6	YA17807	10/01/2005
Dave 7	YA17808	10/01/2005
Dave 8	YA17809	10/01/2005
Dave 17	YA17818	10/01/2005
Dave 18	YA17819	10/01/2005
Dave 26	YA42971	10/01/2005
Dave 29	YA42974	10/01/2005
Dave 30	YA42975	10/01/2005
Dave 31	YA43015	10/01/2005
DG 43	YA14986	10/01/2005
DG 44	YA14987	10/01/2005
DG 45	YA14988	10/01/2005
DG 46	YA14989	10/01/2005
DG 47	YA14990	10/01/2005
DG 48	YA14991	10/01/2005
DG 49	YA14992	10/01/2005
DG 50	YA14993	10/01/2005
DG 51	YA14994	10/01/2005
DG 52	YA14995	10/01/2005
DG 53	YA14996	10/01/2005
DG 54	YA14997	10/01/2005
DG 55	YA14998	10/01/2005
DG 82	YA43044	10/01/2005
DG 83	YA43045	10/01/2005
DG 85	YA43046	10/01/2005
DG 100	YA43061	10/01/2005
DG 101	YA43062	10/01/2005
DG 102	YA43063	10/01/2005
DG 103	YA43064	10/01/2005
Fiji 1	YA63884	10/01/2005
Fiji 2	YB03409	10/01/2005
Fiji 3	YA63886	10/01/2005
Fiji 5	YA63888	10/01/2005
Fiji 6	YA63889	10/01/2005
Jeff 17	YA17842	10/01/2005
Jeff 18	YA17843	10/01/2005
Jeff 33	YA17858	10/01/2005
Jeff 34	YA17859	10/01/2005
Jeff 113	YA42976	10/01/2005
Jeff 114	YA42977	10/01/2005
Jeff 115	YA42978	10/01/2005

Claim Label	Grant #	Current Expiry Date
Jeff 117	YB03408	10/01/2005
Jeff 118	YA42981	10/01/2005
Jeff 120	YA42983	10/01/2005
Mar 1	YA14896	10/01/2005
Mar 2	YA14897	10/01/2005
Mar 3	YA14898	10/01/2005
Mar 4	YA14899	10/01/2005
Mar 5	YA14900	10/01/2005
Mar 6	YA14901	10/01/2005
Mar 7	YA14902	10/01/2005
Mar 8	YA14903	10/01/2005
Mar 9	YA14904	10/01/2005
Mar 10	YA14905	10/01/2005
Mar 11	YA14906	10/01/2005
Mar 12	YA14907	10/01/2005
Mar 14	YA14909	10/01/2005
Mar 15	YA14910	10/01/2005
Mar 16	YA14911	10/01/2005
Mar 17	YA14912	10/01/2005
Mar 18	YA14913	10/01/2005
Mar 19	YA14914	10/01/2005
Mar 20	YA14915	10/01/2005
Mar 21	YA14916	10/01/2005
Mar 22	YA14917	10/01/2005
Mar 24	YA14919	10/01/2005
Mar 31	YA42984	10/01/2005
MAR 33	YA43101	10/01/2005
MAR 34	YA43102	10/01/2005
MAR 35	YA43103	10/01/2005
MAR 36	YA43104	10/01/2005
MAR 37	YA43105	10/01/2005
MAR 38	YA43106	10/01/2005
MAR 39	YA43107	10/01/2005
MAR 40	YA43108	10/01/2005
Mary 1	YA63876	10/01/2005
Mary 2	YA63877	10/01/2005
Mary 3	YA63878	10/01/2005
Mary 4	YA63879	10/01/2005
Mary 5	YA63880	10/01/2005
Mary 6	YA63881	10/01/2005
Mary 7	YA63882	10/01/2005
Mary 8	YA63883	10/01/2005
R & D 1	YA01393	10/01/2005
R & D 2	YA01394	10/01/2005
R & D 3	YA01395	10/01/2005
R & D 4	YA01396	10/01/2005
R & D 5	YA01397	10/01/2005
R & D 6	YA01398	10/01/2005
R & D 7	YA01399	10/01/2005
R & D 8	YA01400	10/01/2005
R & D 10	YA01402	10/01/2005
R & D 12	YA01404	10/01/2005
R & D 14	YA01406	10/01/2005
R & D 15	YA01407	10/01/2005
R & D 16	YA01408	10/01/2005
Roni 1	YB64630	10/01/2005

Claim Label	Grant #	Current Expiry Date
Roni 2	YB64631	10/01/2005
Roni 3	YB64632	10/01/2005
Roni 4	YB64633	10/01/2005
Roni 5	YB64634	10/01/2005
Roni 6	YB64635	10/01/2005
Roni 7	YB64636	10/01/2005
Roni 8	YB64637	10/01/2005
Roni 9	YB64638	10/01/2005
Roni 10	YB64639	10/01/2005
Roni 11	YB64640	10/01/2005
Roni 12	YB64641	10/01/2005
Roni 13	YB64642	10/01/2005
Roni 14	YB64643	10/01/2005
Smoky 1	YA17930	10/01/2005
Smoky 2	YA17931	10/01/2005
Smoky 3	YA17932	10/01/2005
Smoky 4	YA17933	10/01/2005
Smoky 5	YA17934	10/01/2005
Smoky 6	YA17935	10/01/2005
Smoky 7	YA17936	10/01/2005
Smoky 8	YA17937	10/01/2005
Smoky 9	YA17938	10/01/2005
Smoky 10	YA17939	10/01/2005
Smoky 23	YA17952	10/01/2005
Smoky 25	YA17954	10/01/2005
Smoky 26	YA17955	10/01/2005
Smoky 27	YA17956	10/01/2005
Smoky 28	YA17957	10/01/2005
Smoky 29	YA17958	10/01/2005
Smoky 30	YA17959	10/01/2005
Smoky 37	YA17966	10/01/2005
Smoky 38	YA17967	10/01/2005
Smoky 39	YA17968	10/01/2005
Smoky 40	YA17969	10/01/2005
Smoky 41	YA17970	10/01/2005
Smoky 44	YA30072	10/01/2005
Smoky 45	YA30073	10/01/2005
Smoky 46	YA30074	10/01/2005
Smoky 47	YA30075	10/01/2005
Smoky 48	YA17973	10/01/2005
Smoky 49	YA17974	10/01/2005
Smoky 51	YA30076	10/01/2005
Smoky 52	YA30077	10/01/2005
Smoky 53	YA30078	10/01/2005
Smoky 54	YA30079	10/01/2005
Smoky 56	YA17977	10/01/2005
Smoky 58	YA17979	10/01/2005
Smoky 62	YA30080	10/01/2005
Smoky 63	YA30081	10/01/2005
Smoky 64	YA30082	10/01/2005
Smoky 65	YA30083	10/01/2005
Smoky 66	YA17983	10/01/2005
Smoky 67	YA17984	10/01/2005
Smoky 68	YA17985	10/01/2005
Smoky 69	YA17986	10/01/2005
Smoky 70	YA17987	10/01/2005
Smoky 71	YA17988	10/01/2005
Smoky 74	YA30084	10/01/2005
Smoky 75	YA30085	10/01/2005
Smoky 76	YA30086	10/01/2005
Smoky 77	YA30087	10/01/2005
Smoky 78	YA17991	10/01/2005
Smoky 80	YA17993	10/01/2005
Smoky 83	YA43120	10/01/2005
Smoky 84	YA43121	10/01/2005
Smoky 85	YA43122	10/01/2005
Smoky 91	YA43128	10/01/2005
Smoky 92	YA43129	10/01/2005
Smoky 93	YA43130	10/01/2005
Smoky 94	YA43131	10/01/2005
Smoky 95	YA43132	10/01/2005
Smoky 96	YA43133	10/01/2005
Smoky 97	YA43134	10/01/2005
Smoky 98	YA43135	10/01/2005
Smoky 99	YA43136	10/01/2005
Smoky 100	YA43137	10/01/2005
Smoky 107	YA43144	10/01/2005
Smoky 108	YA43145	10/01/2005
Smoky 109	YA43146	10/01/2005
WEST 167	YB18934	10/01/2005
WEST 168	YB18935	10/01/2005
WEST 169	YB18936	10/01/2005
WEST 170	YB18937	10/01/2005
WEST 171	YB18938	10/01/2005
WEST 172	YB18939	10/01/2005
WEST 174	YB18941	10/01/2005
WEST 182	YB18949	10/01/2005
WEST 184	YB18951	10/01/2005
Dub 1574	YC38870	11/01/2005
Dub 1575	YC38871	11/01/2005
Dub 1576	YC38872	11/01/2005
Dub 1577	YC38873	11/01/2005
Dub 1578	YC38874	11/01/2005
Dub 1579	YC38875	11/01/2005
Dub 1580	YC38876	11/01/2005
Dub 1581	YC38877	11/01/2005
Dub 496	YC32493	11/02/2005
Dub 497	YC32494	11/02/2005
Dub 498	YC32495	11/02/2005
Dub 499	YC32496	11/02/2005
Dub 485	YC32482	11/03/2005
Dub 486	YC32483	11/03/2005
Dub 487	YC32484	11/03/2005
Dub 488	YC32485	11/03/2005
Dub 489	YC32486	11/03/2005
Dub 490	YC32487	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 491	YC32488	11/03/2005
Dub 492	YC32489	11/03/2005
Dub 493	YC32490	11/03/2005
Dub 494	YC32491	11/03/2005
Dub 495	YC32492	11/03/2005
Dub 500	YC32497	11/03/2005
Dub 501	YC32498	11/03/2005
Dub 502	YC32499	11/03/2005
Dub 503	YC32500	11/03/2005
Dub 504	YC32501	11/03/2005
Dub 505	YC32502	11/03/2005
Dub 506	YC32503	11/03/2005
Dub 507	YC32504	11/03/2005
Dub 508	YC32505	11/03/2005
Dub 509	YC32506	11/03/2005
Dub 510	YC32507	11/03/2005
Dub 511	YC32508	11/03/2005
Dub 512	YC32509	11/03/2005
Dub 513	YC32510	11/03/2005
Dub 514	YC32511	11/03/2005
Dub 515	YC32512	11/03/2005
Dub 516	YC32513	11/03/2005
Dub 517	YC32514	11/03/2005
Dub 518	YC32515	11/03/2005
Dub 519	YC32516	11/03/2005
Dub 520	YC32517	11/03/2005
Dub 521	YC32518	11/03/2005
Dub 522	YC32519	11/03/2005
Dub 523	YC32520	11/03/2005
Dub 524	YC32521	11/03/2005
Dub 525	YC32522	11/03/2005
Dub 526	YC32523	11/03/2005
Dub 527	YC32524	11/03/2005
Dub 528	YC32525	11/03/2005
Dub 539	YC32536	11/03/2005
Dub 540	YC32537	11/03/2005
Dub 541	YC32538	11/03/2005
Dub 542	YC32539	11/03/2005
Dub 543	YC32540	11/03/2005
Dub 544	YC32541	11/03/2005
Dub 545	YC32542	11/03/2005
Dub 546	YC32543	11/03/2005
Dub 547	YC32544	11/03/2005
Dub 548	YC32545	11/03/2005
Dub 567	YC32564	11/03/2005
Dub 568	YC32565	11/03/2005
Dub 569	YC32566	11/03/2005
Dub 570	YC32567	11/03/2005
Dub 571	YC32568	11/03/2005
Dub 572	YC32569	11/03/2005
Dub 573	YC32570	11/03/2005
Dub 574	YC32571	11/03/2005
Dub 575	YC32572	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 576	YC32573	11/03/2005
Dub 577	YC32574	11/03/2005
Dub 578	YC32575	11/03/2005
Dub 579	YC32576	11/03/2005
Dub 580	YC32577	11/03/2005
Dub 581	YC32578	11/03/2005
Dub 582	YC32579	11/03/2005
Dub 583	YC32580	11/03/2005
Dub 584	YC32581	11/03/2005
Dub 585	YC32582	11/03/2005
Dub 586	YC32583	11/03/2005
Dub 587	YC32584	11/03/2005
Dub 588	YC32585	11/03/2005
Dub 589	YC32586	11/03/2005
Dub 590	YC32587	11/03/2005
Dub 591	YC32588	11/03/2005
Dub 592	YC32589	11/03/2005
Dub 593	YC32590	11/03/2005
Dub 594	YC32591	11/03/2005
Dub 595	YC32592	11/03/2005
Dub 596	YC32593	11/03/2005
Dub 597	YC32594	11/03/2005
Dub 598	YC32595	11/03/2005
Dub 599	YC32596	11/03/2005
Dub 600	YC32597	11/03/2005
Dub 601	YC32598	11/03/2005
Dub 602	YC32599	11/03/2005
Dub 603	YC32600	11/03/2005
Dub 604	YC32601	11/03/2005
Dub 605	YC32602	11/03/2005
Dub 606	YC32603	11/03/2005
Dub 607	YC32604	11/03/2005
Dub 608	YC32605	11/03/2005
Dub 609	YC32606	11/03/2005
Dub 610	YC32607	11/03/2005
Dub 611	YC32608	11/03/2005
Dub 612	YC32609	11/03/2005
Dub 613	YC32610	11/03/2005
Dub 614	YC32611	11/03/2005
Dub 615	YC32612	11/03/2005
Dub 616	YC32613	11/03/2005
Dub 617	YC32614	11/03/2005
Dub 618	YC32615	11/03/2005
Dub 619	YC32616	11/03/2005
Dub 620	YC32617	11/03/2005
Dub 621	YC32618	11/03/2005
Dub 622	YC32619	11/03/2005
Dub 623	YC32620	11/03/2005
Dub 624	YC32621	11/03/2005
Dub 625	YC32622	11/03/2005
Dub 626	YC32623	11/03/2005
Dub 627	YC32624	11/03/2005
Dub 628	YC32625	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 629	YC32626	11/03/2005
Dub 630	YC32627	11/03/2005
Dub 631	YC32628	11/03/2005
Dub 632	YC32629	11/03/2005
Dub 633	YC32630	11/03/2005
Dub 634	YC32631	11/03/2005
Dub 635	YC32632	11/03/2005
Dub 636	YC32633	11/03/2005
Dub 637	YC32634	11/03/2005
Dub 638	YC32635	11/03/2005
Dub 639	YC32636	11/03/2005
Dub 640	YC32637	11/03/2005
Dub 641	YC32638	11/03/2005
Dub 642	YC32639	11/03/2005
Dub 643	YC32640	11/03/2005
Dub 644	YC32641	11/03/2005
Dub 645	YC32642	11/03/2005
Dub 646	YC32643	11/03/2005
Dub 647	YC32644	11/03/2005
Dub 648	YC32645	11/03/2005
Dub 649	YC32646	11/03/2005
Dub 650	YC32647	11/03/2005
Dub 651	YC32648	11/03/2005
Dub 652	YC32649	11/03/2005
Dub 653	YC32650	11/03/2005
Dub 654	YC32651	11/03/2005
Dub 655	YC32652	11/03/2005
Dub 663	YC32660	11/03/2005
Dub 664	YC32661	11/03/2005
Dub 665	YC32662	11/03/2005
Dub 666	YC32663	11/03/2005
Dub 667	YC32664	11/03/2005
Dub 668	YC32665	11/03/2005
Dub 669	YC32666	11/03/2005
Dub 670	YC32667	11/03/2005
Dub 671	YC32668	11/03/2005
Dub 672	YC32669	11/03/2005
Dub 673	YC32670	11/03/2005
Dub 674	YC32671	11/03/2005
Dub 675	YC32672	11/03/2005
Dub 676	YC32673	11/03/2005
Dub 677	YC32674	11/03/2005
Dub 678	YC32675	11/03/2005
Dub 679	YC32676	11/03/2005
Dub 680	YC32677	11/03/2005
Dub 681	YC32678	11/03/2005
Dub 682	YC32679	11/03/2005
Dub 683	YC32680	11/03/2005
Dub 684	YC32681	11/03/2005
Dub 685	YC32682	11/03/2005
Dub 686	YC32683	11/03/2005
Dub 687	YC32684	11/03/2005
Dub 688	YC32685	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 689	YC32686	11/03/2005
Dub 690	YC32687	11/03/2005
Dub 691	YC32688	11/03/2005
Dub 692	YC32689	11/03/2005
Dub 693	YC32690	11/03/2005
Dub 694	YC32691	11/03/2005
Dub 695	YC32692	11/03/2005
Dub 696	YC32693	11/03/2005
Dub 697	YC32694	11/03/2005
Dub 698	YC32695	11/03/2005
Dub 699	YC32696	11/03/2005
Dub 700	YC32697	11/03/2005
Dub 701	YC32698	11/03/2005
Dub 702	YC32699	11/03/2005
Dub 703	YC32700	11/03/2005
Dub 704	YC38001	11/03/2005
Dub 705	YC38002	11/03/2005
Dub 706	YC38003	11/03/2005
Dub 707	YC38004	11/03/2005
Dub 708	YC38005	11/03/2005
Dub 709	YC38006	11/03/2005
Dub 710	YC38007	11/03/2005
Dub 711	YC38008	11/03/2005
Dub 712	YC38009	11/03/2005
Dub 713	YC38010	11/03/2005
Dub 714	YC38011	11/03/2005
Dub 715	YC38012	11/03/2005
Dub 716	YC38013	11/03/2005
Dub 717	YC38014	11/03/2005
Dub 718	YC38015	11/03/2005
Dub 719	YC38016	11/03/2005
Dub 720	YC38017	11/03/2005
Dub 721	YC38018	11/03/2005
Dub 722	YC38019	11/03/2005
Dub 723	YC38020	11/03/2005
Dub 724	YC38021	11/03/2005
Dub 725	YC38022	11/03/2005
Dub 726	YC38023	11/03/2005
Dub 727	YC38024	11/03/2005
Dub 728	YC38025	11/03/2005
Dub 729	YC38026	11/03/2005
Dub 730	YC38027	11/03/2005
Dub 731	YC38028	11/03/2005
Dub 732	YC38029	11/03/2005
Dub 733	YC38030	11/03/2005
Dub 734	YC38031	11/03/2005
Dub 735	YC38032	11/03/2005
Dub 736	YC38033	11/03/2005
Dub 737	YC38034	11/03/2005
Dub 738	YC38035	11/03/2005
Dub 739	YC38036	11/03/2005
Dub 740	YC38037	11/03/2005
Dub 741	YC38038	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 742	YC38039	11/03/2005
Dub 743	YC38040	11/03/2005
Dub 744	YC38041	11/03/2005
Dub 745	YC38042	11/03/2005
Dub 746	YC38043	11/03/2005
Dub 747	YC38044	11/03/2005
Dub 748	YC38045	11/03/2005
Dub 749	YC38046	11/03/2005
Dub 750	YC38047	11/03/2005
Dub 751	YC38048	11/03/2005
Dub 752	YC38049	11/03/2005
Dub 753	YC38050	11/03/2005
Dub 754	YC38051	11/03/2005
Dub 755	YC38052	11/03/2005
Dub 756	YC38053	11/03/2005
Dub 757	YC38054	11/03/2005
Dub 758	YC38055	11/03/2005
Dub 759	YC38056	11/03/2005
Dub 760	YC38057	11/03/2005
Dub 761	YC38058	11/03/2005
Dub 762	YC38059	11/03/2005
Dub 763	YC38060	11/03/2005
Dub 764	YC38061	11/03/2005
Dub 765	YC38062	11/03/2005
Dub 766	YC38063	11/03/2005
Dub 767	YC38064	11/03/2005
Dub 768	YC38065	11/03/2005
Dub 769	YC38066	11/03/2005
Dub 770	YC38067	11/03/2005
Dub 771	YC38068	11/03/2005
Dub 772	YC38069	11/03/2005
Dub 773	YC38070	11/03/2005
Dub 774	YC38071	11/03/2005
Dub 775	YC38072	11/03/2005
Dub 776	YC38073	11/03/2005
Dub 777	YC38074	11/03/2005
Dub 778	YC38075	11/03/2005
Dub 779	YC38076	11/03/2005
Dub 780	YC38077	11/03/2005
Dub 781	YC38078	11/03/2005
Dub 782	YC38079	11/03/2005
Dub 783	YC38080	11/03/2005
Dub 784	YC38081	11/03/2005
Dub 785	YC38082	11/03/2005
Dub 786	YC38083	11/03/2005
Dub 787	YC38084	11/03/2005
Dub 788	YC38085	11/03/2005
Dub 789	YC38086	11/03/2005
Dub 790	YC38087	11/03/2005
Dub 791	YC38088	11/03/2005
Dub 792	YC38089	11/03/2005
Dub 793	YC38090	11/03/2005
Dub 794	YC38091	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 795	YC38092	11/03/2005
Dub 796	YC38093	11/03/2005
Dub 797	YC38094	11/03/2005
Dub 798	YC38095	11/03/2005
Dub 799	YC38096	11/03/2005
Dub 800	YC38097	11/03/2005
Dub 801	YC38098	11/03/2005
Dub 802	YC38099	11/03/2005
Dub 803	YC38100	11/03/2005
Dub 804	YC38101	11/03/2005
Dub 805	YC38102	11/03/2005
Dub 806	YC38103	11/03/2005
Dub 807	YC38104	11/03/2005
Dub 808	YC38105	11/03/2005
Dub 809	YC38106	11/03/2005
Dub 810	YC38107	11/03/2005
Dub 811	YC38108	11/03/2005
Dub 812	YC38109	11/03/2005
Dub 813	YC38110	11/03/2005
Dub 814	YC38111	11/03/2005
Dub 815	YC38112	11/03/2005
Dub 816	YC38113	11/03/2005
Dub 817	YC38114	11/03/2005
Dub 818	YC38115	11/03/2005
Dub 819	YC38116	11/03/2005
Dub 820	YC38117	11/03/2005
Dub 821	YC38118	11/03/2005
Dub 822	YC38119	11/03/2005
Dub 823	YC38120	11/03/2005
Dub 824	YC38121	11/03/2005
Dub 825	YC38122	11/03/2005
Dub 826	YC38123	11/03/2005
Dub 827	YC38124	11/03/2005
Dub 828	YC38125	11/03/2005
Dub 829	YC38126	11/03/2005
Dub 830	YC38127	11/03/2005
Dub 831	YC38128	11/03/2005
Dub 832	YC38129	11/03/2005
Dub 833	YC38130	11/03/2005
Dub 834	YC38131	11/03/2005
Dub 835	YC38132	11/03/2005
Dub 836	YC38133	11/03/2005
Dub 837	YC38134	11/03/2005
Dub 838	YC38135	11/03/2005
Dub 839	YC38136	11/03/2005
Dub 840	YC38137	11/03/2005
Dub 841	YC38138	11/03/2005
Dub 842	YC38139	11/03/2005
Dub 843	YC38140	11/03/2005
Dub 844	YC38141	11/03/2005
Dub 845	YC38142	11/03/2005
Dub 846	YC38143	11/03/2005
Dub 847	YC38144	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 848	YC38145	11/03/2005
Dub 849	YC38146	11/03/2005
Dub 850	YC38147	11/03/2005
Dub 851	YC38148	11/03/2005
Dub 852	YC38149	11/03/2005
Dub 853	YC38150	11/03/2005
Dub 854	YC38151	11/03/2005
Dub 855	YC38152	11/03/2005
Dub 856	YC38153	11/03/2005
Dub 857	YC38154	11/03/2005
Dub 858	YC38155	11/03/2005
Dub 859	YC38156	11/03/2005
Dub 860	YC38157	11/03/2005
Dub 861	YC38158	11/03/2005
Dub 862	YC38159	11/03/2005
Dub 863	YC38160	11/03/2005
Dub 864	YC38161	11/03/2005
Dub 865	YC38162	11/03/2005
Dub 866	YC38163	11/03/2005
Dub 867	YC38164	11/03/2005
Dub 868	YC38165	11/03/2005
Dub 869	YC38166	11/03/2005
Dub 870	YC38167	11/03/2005
Dub 871	YC38168	11/03/2005
Dub 872	YC38169	11/03/2005
Dub 873	YC38170	11/03/2005
Dub 874	YC38171	11/03/2005
Dub 875	YC38172	11/03/2005
Dub 876	YC38173	11/03/2005
Dub 877	YC38174	11/03/2005
Dub 878	YC38175	11/03/2005
Dub 879	YC38176	11/03/2005
Dub 880	YC38177	11/03/2005
Dub 881	YC38178	11/03/2005
Dub 882	YC38179	11/03/2005
Dub 883	YC38180	11/03/2005
Dub 884	YC38181	11/03/2005
Dub 885	YC38182	11/03/2005
Dub 886	YC38183	11/03/2005
Dub 887	YC38184	11/03/2005
Dub 888	YC38185	11/03/2005
Dub 889	YC38186	11/03/2005
Dub 890	YC38187	11/03/2005
Dub 891	YC38188	11/03/2005
Dub 892	YC38189	11/03/2005
Dub 893	YC38190	11/03/2005
Dub 894	YC38191	11/03/2005
Dub 895	YC38192	11/03/2005
Dub 896	YC38193	11/03/2005
Dub 897	YC38194	11/03/2005
Dub 898	YC38195	11/03/2005
Dub 899	YC38196	11/03/2005
Dub 900	YC38197	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 901	YC38198	11/03/2005
Dub 902	YC38199	11/03/2005
Dub 903	YC38200	11/03/2005
Dub 904	YC38201	11/03/2005
Dub 905	YC38202	11/03/2005
Dub 906	YC38203	11/03/2005
Dub 907	YC38204	11/03/2005
Dub 908	YC38205	11/03/2005
Dub 909	YC38206	11/03/2005
Dub 910	YC38207	11/03/2005
Dub 911	YC38208	11/03/2005
Dub 912	YC38209	11/03/2005
Dub 913	YC38210	11/03/2005
Dub 914	YC38211	11/03/2005
Dub 915	YC38212	11/03/2005
Dub 916	YC38213	11/03/2005
Dub 917	YC38214	11/03/2005
Dub 918	YC38215	11/03/2005
Dub 919	YC38216	11/03/2005
Dub 920	YC38217	11/03/2005
Dub 921	YC38218	11/03/2005
Dub 922	YC38219	11/03/2005
Dub 923	YC38220	11/03/2005
Dub 924	YC38221	11/03/2005
Dub 925	YC38222	11/03/2005
Dub 926	YC38223	11/03/2005
Dub 927	YC38224	11/03/2005
Dub 928	YC38225	11/03/2005
Dub 929	YC38226	11/03/2005
Dub 930	YC38227	11/03/2005
Dub 931	YC38228	11/03/2005
Dub 932	YC38229	11/03/2005
Dub 933	YC38230	11/03/2005
Dub 934	YC38231	11/03/2005
Dub 935	YC38232	11/03/2005
Dub 936	YC38233	11/03/2005
Dub 937	YC38234	11/03/2005
Dub 938	YC38235	11/03/2005
Dub 939	YC38236	11/03/2005
Dub 940	YC38237	11/03/2005
Dub 941	YC38238	11/03/2005
Dub 942	YC38239	11/03/2005
Dub 943	YC38240	11/03/2005
Dub 944	YC38241	11/03/2005
Dub 945	YC38242	11/03/2005
Dub 946	YC38243	11/03/2005
Dub 947	YC38244	11/03/2005
Dub 948	YC38245	11/03/2005
Dub 949	YC38246	11/03/2005
Dub 950	YC38247	11/03/2005
Dub 951	YC38248	11/03/2005
Dub 952	YC38249	11/03/2005
Dub 953	YC38250	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 954	YC38251	11/03/2005
Dub 955	YC38252	11/03/2005
Dub 956	YC38253	11/03/2005
Dub 957	YC38254	11/03/2005
Dub 958	YC38255	11/03/2005
Dub 959	YC38256	11/03/2005
Dub 960	YC38257	11/03/2005
Dub 961	YC38258	11/03/2005
Dub 962	YC38259	11/03/2005
Dub 963	YC38260	11/03/2005
Dub 964	YC38261	11/03/2005
Dub 965	YC38262	11/03/2005
Dub 966	YC38263	11/03/2005
Dub 967	YC38264	11/03/2005
Dub 968	YC38265	11/03/2005
Dub 969	YC38266	11/03/2005
Dub 970	YC38267	11/03/2005
Dub 971	YC38268	11/03/2005
Dub 972	YC38269	11/03/2005
Dub 973	YC38270	11/03/2005
Dub 974	YC38271	11/03/2005
Dub 975	YC38272	11/03/2005
Dub 976	YC38273	11/03/2005
Dub 977	YC38274	11/03/2005
Dub 978	YC38275	11/03/2005
Dub 979	YC38276	11/03/2005
Dub 980	YC38277	11/03/2005
Dub 981	YC38278	11/03/2005
Dub 982	YC38279	11/03/2005
Dub 983	YC38280	11/03/2005
Dub 984	YC38281	11/03/2005
Dub 985	YC38282	11/03/2005
Dub 986	YC38283	11/03/2005
Dub 987	YC38284	11/03/2005
Dub 988	YC38285	11/03/2005
Dub 989	YC38286	11/03/2005
Dub 990	YC38287	11/03/2005
Dub 991	YC38288	11/03/2005
Dub 992	YC38289	11/03/2005
Dub 993	YC38290	11/03/2005
Dub 994	YC38291	11/03/2005
Dub 995	YC38292	11/03/2005
Dub 996	YC38293	11/03/2005
Dub 997	YC38294	11/03/2005
Dub 998	YC38295	11/03/2005
Dub 999	YC38296	11/03/2005
Dub 1000	YC38297	11/03/2005
Dub 1001	YC38298	11/03/2005
Dub 1002	YC38299	11/03/2005
Dub 1003	YC38300	11/03/2005
Dub 1004	YC38301	11/03/2005
Dub 1005	YC38302	11/03/2005
Dub 1006	YC38303	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 1007	YC38304	11/03/2005
Dub 1008	YC38305	11/03/2005
Dub 1009	YC38306	11/03/2005
Dub 1010	YC38307	11/03/2005
Dub 1011	YC38308	11/03/2005
Dub 1012	YC38309	11/03/2005
Dub 1013	YC38310	11/03/2005
Dub 1014	YC38311	11/03/2005
Dub 1015	YC38312	11/03/2005
Dub 1016	YC38313	11/03/2005
Dub 1017	YC38314	11/03/2005
Dub 1018	YC38315	11/03/2005
Dub 1019	YC38316	11/03/2005
Dub 1020	YC38317	11/03/2005
Dub 1021	YC38318	11/03/2005
Dub 1022	YC38319	11/03/2005
Dub 1023	YC38320	11/03/2005
Dub 1024	YC38321	11/03/2005
Dub 1025	YC38322	11/03/2005
Dub 1026	YC38323	11/03/2005
Dub 1027	YC38324	11/03/2005
Dub 1028	YC38325	11/03/2005
Dub 1029	YC38326	11/03/2005
Dub 1030	YC38327	11/03/2005
Dub 1031	YC38328	11/03/2005
Dub 1032	YC38329	11/03/2005
Dub 1033	YC38330	11/03/2005
Dub 1034	YC38331	11/03/2005
Dub 1035	YC38332	11/03/2005
Dub 1036	YC38333	11/03/2005
Dub 1037	YC38334	11/03/2005
Dub 1038	YC38335	11/03/2005
Dub 1039	YC38336	11/03/2005
Dub 1040	YC38337	11/03/2005
Dub 1041	YC38338	11/03/2005
Dub 1042	YC38339	11/03/2005
Dub 1043	YC38340	11/03/2005
Dub 1044	YC38341	11/03/2005
Dub 1045	YC38342	11/03/2005
Dub 1046	YC38343	11/03/2005
Dub 1047	YC38344	11/03/2005
Dub 1048	YC38345	11/03/2005
Dub 1049	YC38346	11/03/2005
Dub 1050	YC38347	11/03/2005
Dub 1051	YC38348	11/03/2005
Dub 1052	YC38349	11/03/2005
Dub 1053	YC38350	11/03/2005
Dub 1054	YC38351	11/03/2005
Dub 1055	YC38352	11/03/2005
Dub 1056	YC38353	11/03/2005
Dub 1057	YC38354	11/03/2005
Dub 1058	YC38355	11/03/2005
Dub 1059	YC38356	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 1060	YC38357	11/03/2005
Dub 1061	YC38358	11/03/2005
Dub 1062	YC38359	11/03/2005
Dub 1063	YC38360	11/03/2005
Dub 1064	YC38361	11/03/2005
Dub 1065	YC38362	11/03/2005
Dub 1066	YC38363	11/03/2005
Dub 1067	YC38364	11/03/2005
Dub 1068	YC38365	11/03/2005
Dub 1069	YC38366	11/03/2005
Dub 1070	YC38367	11/03/2005
Dub 1071	YC38368	11/03/2005
Dub 1072	YC38369	11/03/2005
Dub 1073	YC38370	11/03/2005
Dub 1074	YC38371	11/03/2005
Dub 1075	YC38372	11/03/2005
Dub 1076	YC38373	11/03/2005
Dub 1077	YC38374	11/03/2005
Dub 1078	YC38375	11/03/2005
Dub 1079	YC38376	11/03/2005
Dub 1080	YC38377	11/03/2005
Dub 1081	YC38378	11/03/2005
Dub 1082	YC38379	11/03/2005
Dub 1083	YC38380	11/03/2005
Dub 1084	YC38381	11/03/2005
Dub 1085	YC38382	11/03/2005
Dub 1086	YC38383	11/03/2005
Dub 1087	YC38384	11/03/2005
Dub 1088	YC38385	11/03/2005
Dub 1089	YC38386	11/03/2005
Dub 1090	YC38387	11/03/2005
Dub 1091	YC38388	11/03/2005
Dub 1092	YC38389	11/03/2005
Dub 1093	YC38390	11/03/2005
Dub 1094	YC38391	11/03/2005
Dub 1095	YC38392	11/03/2005
Dub 1096	YC38393	11/03/2005
Dub 1097	YC38394	11/03/2005
Dub 1098	YC38395	11/03/2005
Dub 1099	YC38396	11/03/2005
Dub 1100	YC38397	11/03/2005
Dub 1101	YC38398	11/03/2005
Dub 1102	YC38399	11/03/2005
Dub 1103	YC38400	11/03/2005
Dub 1104	YC38401	11/03/2005
Dub 1105	YC38402	11/03/2005
Dub 1106	YC38403	11/03/2005
Dub 1107	YC38404	11/03/2005
Dub 1108	YC38405	11/03/2005
Dub 1109	YC38406	11/03/2005
Dub 1110	YC38407	11/03/2005
Dub 1111	YC38408	11/03/2005
Dub 1112	YC38409	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 1113	YC38410	11/03/2005
Dub 1114	YC38411	11/03/2005
Dub 1115	YC38412	11/03/2005
Dub 1116	YC38413	11/03/2005
Dub 1117	YC38414	11/03/2005
Dub 1118	YC38415	11/03/2005
Dub 1119	YC38416	11/03/2005
Dub 1120	YC38417	11/03/2005
Dub 1121	YC38418	11/03/2005
Dub 1122	YC38419	11/03/2005
Dub 1123	YC38420	11/03/2005
Dub 1124	YC38421	11/03/2005
Dub 1125	YC38422	11/03/2005
Dub 1128	YC38425	11/03/2005
Dub 1129	YC38426	11/03/2005
Dub 1130	YC38427	11/03/2005
Dub 1131	YC38428	11/03/2005
Dub 1132	YC38429	11/03/2005
Dub 1133	YC38430	11/03/2005
Dub 1134	YC38431	11/03/2005
Dub 1135	YC38432	11/03/2005
Dub 1136	YC38433	11/03/2005
Dub 1137	YC38434	11/03/2005
Dub 1138	YC38435	11/03/2005
Dub 1139	YC38436	11/03/2005
Dub 1140	YC38437	11/03/2005
Dub 1141	YC38438	11/03/2005
Dub 1142	YC38439	11/03/2005
Dub 1143	YC38440	11/03/2005
Dub 1144	YC38441	11/03/2005
Dub 1145	YC38442	11/03/2005
Dub 1146	YC38443	11/03/2005
Dub 1147	YC38444	11/03/2005
Dub 1148	YC38445	11/03/2005
Dub 1149	YC38446	11/03/2005
Dub 1150	YC38447	11/03/2005
Dub 1151	YC38448	11/03/2005
Dub 1152	YC38449	11/03/2005
Dub 1153	YC38450	11/03/2005
Dub 1154	YC38451	11/03/2005
Dub 1155	YC38452	11/03/2005
Dub 1156	YC38453	11/03/2005
Dub 1157	YC38454	11/03/2005
Dub 1158	YC38455	11/03/2005
Dub 1159	YC38456	11/03/2005
Dub 1160	YC38457	11/03/2005
Dub 1161	YC38458	11/03/2005
Dub 1162	YC38459	11/03/2005
Dub 1163	YC38460	11/03/2005
Dub 1164	YC38461	11/03/2005
Dub 1165	YC38462	11/03/2005
Dub 1166	YC38463	11/03/2005
Dub 1167	YC38464	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 1168	YC38465	11/03/2005
Dub 1169	YC38466	11/03/2005
Dub 1170	YC38467	11/03/2005
Dub 1171	YC38468	11/03/2005
Dub 1172	YC38469	11/03/2005
Dub 1173	YC38470	11/03/2005
Dub 1174	YC38471	11/03/2005
Dub 1175	YC38472	11/03/2005
Dub 1176	YC38473	11/03/2005
Dub 1177	YC38474	11/03/2005
Dub 1178	YC38475	11/03/2005
Dub 1179	YC38476	11/03/2005
Dub 1180	YC38477	11/03/2005
Dub 1181	YC38478	11/03/2005
Dub 1182	YC38479	11/03/2005
Dub 1183	YC38480	11/03/2005
Dub 1184	YC38481	11/03/2005
Dub 1185	YC38482	11/03/2005
Dub 1186	YC38483	11/03/2005
Dub 1187	YC38484	11/03/2005
Dub 1188	YC38485	11/03/2005
Dub 1189	YC38486	11/03/2005
Dub 1190	YC38487	11/03/2005
Dub 1191	YC38488	11/03/2005
Dub 1192	YC38489	11/03/2005
Dub 1193	YC38490	11/03/2005
Dub 1194	YC38491	11/03/2005
Dub 1195	YC38492	11/03/2005
Dub 1210	YC38507	11/03/2005
Dub 1211	YC38508	11/03/2005
Dub 1212	YC38509	11/03/2005
Dub 1213	YC38510	11/03/2005
Dub 1214	YC38511	11/03/2005
Dub 1215	YC38512	11/03/2005
Dub 1216	YC38513	11/03/2005
Dub 1217	YC38514	11/03/2005
Dub 1218	YC38515	11/03/2005
Dub 1219	YC38516	11/03/2005
Dub 1220	YC38517	11/03/2005
Dub 1221	YC38518	11/03/2005
Dub 1222	YC38519	11/03/2005
Dub 1223	YC38520	11/03/2005
Dub 1224	YC38521	11/03/2005
Dub 1225	YC38522	11/03/2005
Dub 1226	YC38523	11/03/2005
Dub 1227	YC38524	11/03/2005
Dub 1228	YC38525	11/03/2005
Dub 1229	YC38526	11/03/2005
Dub 1230	YC38527	11/03/2005
Dub 1231	YC38528	11/03/2005
Dub 1232	YC38529	11/03/2005
Dub 1233	YC38530	11/03/2005
Dub 1234	YC38531	11/03/2005

Claim Label	Grant #	Current Expiry Date
Dub 1235	YC38532	11/03/2005
Dub 1236	YC38533	11/03/2005
Dub 1237	YC38534	11/03/2005
Dub 1238	YC38535	11/03/2005
Dub 1239	YC38536	11/03/2005
Dub 1240	YC38537	11/03/2005
Dub 1241	YC38538	11/03/2005
Dub 1242	YC38539	11/03/2005
Dub 1243	YC38540	11/03/2005
Dub 1244	YC38541	11/03/2005
Dub 1245	YC38542	11/03/2005
Dub 1246	YC38543	11/03/2005
Dub 1247	YC38544	11/03/2005
Dub 1248	YC38545	11/03/2005
Dub 1249	YC38546	11/03/2005
Dub 1250	YC38547	11/03/2005
Dub 1251	YC38548	11/03/2005
Dub 1252	YC38549	11/03/2005
Dub 1253	YC38550	11/03/2005
Dub 1254	YC38551	11/03/2005
Dub 1255	YC38552	11/03/2005
Dub 1256	YC38553	11/03/2005
Dub 1257	YC38554	11/03/2005
Dub 1258	YC38555	11/03/2005
Dub 1259	YC38556	11/03/2005
Dub 1260	YC38557	11/03/2005
Dub 1261	YC38558	11/03/2005
Dub 1262	YC38559	11/03/2005
Dub 1263	YC38560	11/03/2005
Dub 1264	YC38561	11/03/2005
Dub 1265	YC38562	11/03/2005
Dub 1266	YC38563	11/03/2005
Dub 1267	YC38564	11/03/2005
Dub 1268	YC38565	11/03/2005
Dub 1269	YC38566	11/03/2005
Dub 1270	YC38567	11/03/2005
Dub 1271	YC38568	11/03/2005
Dub 1272	YC38569	11/03/2005
Dub 1273	YC38570	11/03/2005
Dub 1274	YC38571	11/03/2005
Dub 1275	YC38572	11/03/2005
Dub 1276	YC38573	11/03/2005
Dub 1277	YC38574	11/03/2005
Dub 1278	YC38575	11/03/2005
Dub 1279	YC38576	11/03/2005
Dub 660	YC32657	11/05/2005
Dub 661	YC32658	11/05/2005
Dub 662	YC32659	11/05/2005
Dub 1126	YC38423	11/05/2005
Dub 1127	YC38424	11/05/2005
Dub 1196	YC38493	11/05/2005
Dub 1197	YC38494	11/05/2005
Dub 1198	YC38495	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1199	YC38496	11/05/2005
Dub 1200	YC38497	11/05/2005
Dub 1201	YC38498	11/05/2005
Dub 1202	YC38499	11/05/2005
Dub 1203	YC38500	11/05/2005
Dub 1204	YC38501	11/05/2005
Dub 1205	YC38502	11/05/2005
Dub 1206	YC38503	11/05/2005
Dub 1207	YC38504	11/05/2005
Dub 1208	YC38505	11/05/2005
Dub 1209	YC38506	11/05/2005
Dub 1280	YC38577	11/05/2005
Dub 1281	YC38578	11/05/2005
Dub 1282	YC38579	11/05/2005
Dub 1283	YC38580	11/05/2005
Dub 1284	YC38581	11/05/2005
Dub 1285	YC38582	11/05/2005
Dub 1286	YC38583	11/05/2005
Dub 1287	YC38584	11/05/2005
Dub 1288	YC38585	11/05/2005
Dub 1289	YC38586	11/05/2005
Dub 1290	YC38587	11/05/2005
Dub 1291	YC38588	11/05/2005
Dub 1292	YC38589	11/05/2005
Dub 1293	YC38590	11/05/2005
Dub 1294	YC38591	11/05/2005
Dub 1295	YC38592	11/05/2005
Dub 1296	YC38593	11/05/2005
Dub 1297	YC38594	11/05/2005
Dub 1298	YC38595	11/05/2005
Dub 1299	YC38596	11/05/2005
Dub 1300	YC38597	11/05/2005
Dub 1301	YC38598	11/05/2005
Dub 1302	YC38599	11/05/2005
Dub 1303	YC38600	11/05/2005
Dub 1304	YC38601	11/05/2005
Dub 1305	YC38602	11/05/2005
Dub 1306	YC38603	11/05/2005
Dub 1307	YC38604	11/05/2005
Dub 1308	YC38605	11/05/2005
Dub 1309	YC38606	11/05/2005
Dub 1310	YC38607	11/05/2005
Dub 1311	YC38608	11/05/2005
Dub 1312	YC38609	11/05/2005
Dub 1313	YC38610	11/05/2005
Dub 1314	YC38611	11/05/2005
Dub 1315	YC38612	11/05/2005
Dub 1316	YC38613	11/05/2005
Dub 1317	YC38614	11/05/2005
Dub 1318	YC38615	11/05/2005
Dub 1319	YC38616	11/05/2005
Dub 1320	YC38617	11/05/2005
Dub 1321	YC38618	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1322	YC38619	11/05/2005
Dub 1323	YC38620	11/05/2005
Dub 1324	YC38621	11/05/2005
Dub 1325	YC38622	11/05/2005
Dub 1326	YC38623	11/05/2005
Dub 1327	YC38624	11/05/2005
Dub 1328	YC38625	11/05/2005
Dub 1329	YC38626	11/05/2005
Dub 1330	YC38627	11/05/2005
Dub 1331	YC38628	11/05/2005
Dub 1332	YC38629	11/05/2005
Dub 1333	YC38630	11/05/2005
Dub 1334	YC38631	11/05/2005
Dub 1335	YC38632	11/05/2005
Dub 1336	YC38633	11/05/2005
Dub 1337	YC38634	11/05/2005
Dub 1338	YC38635	11/05/2005
Dub 1339	YC38636	11/05/2005
Dub 1340	YC38637	11/05/2005
Dub 1341	YC38638	11/05/2005
Dub 1342	YC38639	11/05/2005
Dub 1343	YC38640	11/05/2005
Dub 1344	YC38641	11/05/2005
Dub 1346	YC38642	11/05/2005
Dub 1347	YC38643	11/05/2005
Dub 1348	YC38644	11/05/2005
Dub 1349	YC38645	11/05/2005
Dub 1350	YC38646	11/05/2005
Dub 1351	YC38647	11/05/2005
Dub 1352	YC38648	11/05/2005
Dub 1353	YC38649	11/05/2005
Dub 1354	YC38650	11/05/2005
Dub 1355	YC38651	11/05/2005
Dub 1364	YC38660	11/05/2005
Dub 1365	YC38661	11/05/2005
Dub 1366	YC38662	11/05/2005
Dub 1367	YC38663	11/05/2005
Dub 1368	YC38664	11/05/2005
Dub 1369	YC38665	11/05/2005
Dub 1370	YC38666	11/05/2005
Dub 1371	YC38667	11/05/2005
Dub 1372	YC38668	11/05/2005
Dub 1373	YC38669	11/05/2005
Dub 1374	YC38670	11/05/2005
Dub 1375	YC38671	11/05/2005
Dub 1376	YC38672	11/05/2005
Dub 1377	YC38673	11/05/2005
Dub 1378	YC38674	11/05/2005
Dub 1379	YC38675	11/05/2005
Dub 1380	YC38676	11/05/2005
Dub 1381	YC38677	11/05/2005
Dub 1382	YC38678	11/05/2005
Dub 1383	YC38679	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1384	YC38680	11/05/2005
Dub 1385	YC38681	11/05/2005
Dub 1386	YC38682	11/05/2005
Dub 1387	YC38683	11/05/2005
Dub 1388	YC38684	11/05/2005
Dub 1389	YC38685	11/05/2005
Dub 1400	YC38696	11/05/2005
Dub 1401	YC38697	11/05/2005
Dub 1402	YC38698	11/05/2005
Dub 1403	YC38699	11/05/2005
Dub 1404	YC38700	11/05/2005
Dub 1405	YC38701	11/05/2005
Dub 1406	YC38702	11/05/2005
Dub 1407	YC38703	11/05/2005
Dub 1408	YC38704	11/05/2005
Dub 1409	YC38705	11/05/2005
Dub 1410	YC38706	11/05/2005
Dub 1411	YC38707	11/05/2005
Dub 1412	YC38708	11/05/2005
Dub 1413	YC38709	11/05/2005
Dub 1414	YC38710	11/05/2005
Dub 1415	YC38711	11/05/2005
Dub 1416	YC38712	11/05/2005
Dub 1417	YC38713	11/05/2005
Dub 1418	YC38714	11/05/2005
Dub 1419	YC38715	11/05/2005
Dub 1420	YC38716	11/05/2005
Dub 1421	YC38717	11/05/2005
Dub 1422	YC38718	11/05/2005
Dub 1423	YC38719	11/05/2005
Dub 1424	YC38720	11/05/2005
Dub 1425	YC38721	11/05/2005
Dub 1426	YC38722	11/05/2005
Dub 1427	YC38723	11/05/2005
Dub 1428	YC38724	11/05/2005
Dub 1429	YC38725	11/05/2005
Dub 1430	YC38726	11/05/2005
Dub 1431	YC38727	11/05/2005
Dub 1432	YC38728	11/05/2005
Dub 1433	YC38729	11/05/2005
Dub 1434	YC38730	11/05/2005
Dub 1435	YC38731	11/05/2005
Dub 1436	YC38732	11/05/2005
Dub 1437	YC38733	11/05/2005
Dub 1438	YC38734	11/05/2005
Dub 1439	YC38735	11/05/2005
Dub 1440	YC38736	11/05/2005
Dub 1441	YC38737	11/05/2005
Dub 1442	YC38738	11/05/2005
Dub 1443	YC38739	11/05/2005
Dub 1444	YC38740	11/05/2005
Dub 1445	YC38741	11/05/2005
Dub 1446	YC38742	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1447	YC38743	11/05/2005
Dub 1448	YC38744	11/05/2005
Dub 1449	YC38745	11/05/2005
Dub 1450	YC38746	11/05/2005
Dub 1451	YC38747	11/05/2005
Dub 1452	YC38748	11/05/2005
Dub 1453	YC38749	11/05/2005
Dub 1454	YC38750	11/05/2005
Dub 1455	YC38751	11/05/2005
Dub 1456	YC38752	11/05/2005
Dub 1457	YC38753	11/05/2005
Dub 1458	YC38754	11/05/2005
Dub 1459	YC38755	11/05/2005
Dub 1460	YC38756	11/05/2005
Dub 1461	YC38757	11/05/2005
Dub 1462	YC38758	11/05/2005
Dub 1463	YC38759	11/05/2005
Dub 1464	YC38760	11/05/2005
Dub 1465	YC38761	11/05/2005
Dub 1466	YC38762	11/05/2005
Dub 1467	YC38763	11/05/2005
Dub 1468	YC38764	11/05/2005
Dub 1469	YC38765	11/05/2005
Dub 1470	YC38766	11/05/2005
Dub 1471	YC38767	11/05/2005
Dub 1472	YC38768	11/05/2005
Dub 1473	YC38769	11/05/2005
Dub 1474	YC38770	11/05/2005
Dub 1475	YC38771	11/05/2005
Dub 1476	YC38772	11/05/2005
Dub 1477	YC38773	11/05/2005
Dub 1478	YC38774	11/05/2005
Dub 1479	YC38775	11/05/2005
Dub 1480	YC38776	11/05/2005
Dub 1481	YC38777	11/05/2005
Dub 1482	YC38778	11/05/2005
Dub 1483	YC38779	11/05/2005
Dub 1484	YC38780	11/05/2005
Dub 1485	YC38781	11/05/2005
Dub 1486	YC38782	11/05/2005
Dub 1487	YC38783	11/05/2005
Dub 1488	YC38784	11/05/2005
Dub 1489	YC38785	11/05/2005
Dub 1490	YC38786	11/05/2005
Dub 1491	YC38787	11/05/2005
Dub 1492	YC38788	11/05/2005
Dub 1493	YC38789	11/05/2005
Dub 1494	YC38790	11/05/2005
Dub 1495	YC38791	11/05/2005
Dub 1496	YC38792	11/05/2005
Dub 1497	YC38793	11/05/2005
Dub 1498	YC38794	11/05/2005
Dub 1499	YC38795	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1500	YC38796	11/05/2005
Dub 1501	YC38797	11/05/2005
Dub 1502	YC38798	11/05/2005
Dub 1503	YC38799	11/05/2005
Dub 1504	YC38800	11/05/2005
Dub 1505	YC38801	11/05/2005
Dub 1506	YC38802	11/05/2005
Dub 1507	YC38803	11/05/2005
Dub 1508	YC38804	11/05/2005
Dub 1509	YC38805	11/05/2005
Dub 1510	YC38806	11/05/2005
Dub 1511	YC38807	11/05/2005
Dub 1512	YC38808	11/05/2005
Dub 1513	YC38809	11/05/2005
Dub 1514	YC38810	11/05/2005
Dub 1515	YC38811	11/05/2005
Dub 1516	YC38812	11/05/2005
Dub 1517	YC38813	11/05/2005
Dub 1518	YC38814	11/05/2005
Dub 1519	YC38815	11/05/2005
Dub 1520	YC38816	11/05/2005
Dub 1521	YC38817	11/05/2005
Dub 1522	YC38818	11/05/2005
Dub 1523	YC38819	11/05/2005
Dub 1524	YC38820	11/05/2005
Dub 1525	YC38821	11/05/2005
Dub 1526	YC38822	11/05/2005
Dub 1527	YC38823	11/05/2005
Dub 1528	YC38824	11/05/2005
Dub 1529	YC38825	11/05/2005
Dub 1530	YC38826	11/05/2005
Dub 1531	YC38827	11/05/2005
Dub 1532	YC38828	11/05/2005
Dub 1533	YC38829	11/05/2005
Dub 1534	YC38830	11/05/2005
Dub 1535	YC38831	11/05/2005
Dub 1536	YC38832	11/05/2005
Dub 1537	YC38833	11/05/2005
Dub 1538	YC38834	11/05/2005
Dub 1539	YC38835	11/05/2005
Dub 1540	YC38836	11/05/2005
Dub 1541	YC38837	11/05/2005
Dub 1542	YC38838	11/05/2005
Dub 1543	YC38839	11/05/2005
Dub 1544	YC38840	11/05/2005
Dub 1545	YC38841	11/05/2005
Dub 1546	YC38842	11/05/2005
Dub 1547	YC38843	11/05/2005
Dub 1548	YC38844	11/05/2005
Dub 1549	YC38845	11/05/2005
Dub 1550	YC38846	11/05/2005
Dub 1551	YC38847	11/05/2005
Dub 1552	YC38848	11/05/2005

Claim Label	Grant #	Current Expiry Date
Dub 1553	YC38849	11/05/2005
Dub 1554	YC38850	11/05/2005
Dub 1555	YC38851	11/05/2005
Dub 1556	YC38852	11/05/2005
Dub 1557	YC38853	11/05/2005
Dub 1558	YC38854	11/05/2005
Dub 1559	YC38855	11/05/2005
Dub 1560	YC38856	11/05/2005
Dub 1561	YC38857	11/05/2005
Dub 1562	YC38858	11/05/2005
Dub 1563	YC38859	11/05/2005
Dub 1564	YC38860	11/05/2005
Dub 1565	YC38861	11/05/2005
Dub 1566	YC38862	11/05/2005
Dub 1567	YC38863	11/05/2005
Dub 1568	YC38864	11/05/2005
Dub 1569	YC38865	11/05/2005
Dub 1570	YC38866	11/05/2005
Dub 1571	YC38867	11/05/2005
Dub 1572	YC38868	11/05/2005
Dub 1573	YC38869	11/05/2005
Dub 481	YC32478	10/06/2005
Dub 482	YC32479	10/06/2005
Dub 483	YC32480	10/06/2005
Dub 484	YC32481	10/06/2005
Dub 656	YC32653	11/08/2005
Dub 657	YC32654	11/08/2005
Dub 658	YC32655	11/08/2005
Dub 659	YC32656	11/08/2005
Dub 1356	YC38652	11/08/2005
Dub 1357	YC38653	11/08/2005
Dub 1358	YC38654	11/08/2005
Dub 1359	YC38655	11/08/2005
Dub 1360	YC38656	11/08/2005
Dub 1361	YC38657	11/08/2005
Dub 1362	YC38658	11/08/2005
Dub 1363	YC38659	11/08/2005
Dub 1394	YC38690	11/08/2005
Dub 1395	YC38691	11/08/2005
Dub 1396	YC38692	11/08/2005
Dub 1397	YC38693	11/08/2005
Dub 1398	YC38694	11/08/2005
Dub 1399	YC38695	11/08/2005
Dub 1582	YC38878	11/08/2005
Olive	GR 1054	01/01/9999
Dub 258	YC11332	1/16/2007
Dub 324	YC11398	1/16/2007
Dub 357	YC11431	1/16/2007
Dub 358	YC11432	1/16/2007
Dub 359	YC11433	1/16/2007
Dub 360	YC11434	1/16/2007
Dub 402	YC11476	1/16/2007
Dub 404	YC11478	1/16/2007

Claim Label	Grant #	Current Expiry Date
Dub 136	YC11210	1/16/2008
Dub 137	YC11211	1/16/2008
Dub 138	YC11212	1/16/2008
Dub 139	YC11213	1/16/2008
Dub 169	YC11243	1/16/2008
Dub 170	YC11244	1/16/2008
Dub 171	YC11245	1/16/2008
Dub 172	YC11246	1/16/2008
Dub 173	YC11247	1/16/2008
Dub 174	YC11248	1/16/2008
Dub 175	YC11249	1/16/2008
Dub 176	YC11250	1/16/2008
Dub 177	YC11251	1/16/2008
Dub 178	YC11252	1/16/2008
Dub 204	YC11278	1/16/2008
Dub 205	YC11279	1/16/2008
Dub 206	YC11280	1/16/2008
Dub 207	YC11281	1/16/2008
Dub 208	YC11282	1/16/2008
Dub 219	YC11293	1/16/2008
Dub 223	YC11297	1/16/2008
Dub 231	YC11305	1/16/2008
Dub 232	YC11306	1/16/2008
Dub 257	YC11331	1/16/2008
Dub 259	YC11333	1/16/2008
Dub 260	YC11334	1/16/2008
Dub 262	YC11336	1/16/2008
Dub 263	YC11337	1/16/2008
Dub 264	YC11338	1/16/2008
Dub 265	YC11339	1/16/2008
Dub 266	YC11340	1/16/2008
Dub 281	YC11355	1/16/2008
Dub 282	YC11356	1/16/2008
Dub 283	YC11357	1/16/2008
Dub 284	YC11358	1/16/2008
Dub 285	YC11359	1/16/2008
Dub 286	YC11360	1/16/2008
Dub 287	YC11361	1/16/2008
Dub 288	YC11362	1/16/2008
Dub 290	YC11364	1/16/2008
Dub 295	YC11369	1/16/2008
Dub 309	YC11383	1/16/2008
Dub 310	YC11384	1/16/2008
Dub 311	YC11385	1/16/2008
Dub 321	YC11395	1/16/2008
Dub 322	YC11396	1/16/2008
Dub 323	YC11397	1/16/2008
Dub 326	YC11400	1/16/2008
Dub 327	YC11401	1/16/2008
Dub 328	YC11402	1/16/2008
Dub 329	YC11403	1/16/2008
Dub 346	YC11420	1/16/2008
Dub 348	YC11422	1/16/2008

Claim Label	Grant #	Current Expiry Date
Dub 350	YC11424	1/16/2008
Dub 354	YC11428	1/16/2008
Dub 356	YC11430	1/16/2008
Dub 361	YC11435	1/16/2008
Dub 362	YC11436	1/16/2008
Dub 363	YC11437	1/16/2008
Dub 364	YC11438	1/16/2008
Dub 369	YC11443	1/16/2008
Dub 371	YC11445	1/16/2008
Dub 372	YC11446	1/16/2008
Dub 373	YC11447	1/16/2008
Dub 374	YC11448	1/16/2008
Dub 391	YC11465	1/16/2008
Dub 392	YC11466	1/16/2008
Dub 393	YC11467	1/16/2008
Dub 394	YC11468	1/16/2008
Dub 395	YC11469	1/16/2008
Dub 396	YC11470	1/16/2008
Dub 398	YC11472	1/16/2008
Dub 401	YC11475	1/16/2008
Dub 403	YC11477	1/16/2008
Dub 405	YC11479	1/16/2008
Dub 406	YC11480	1/16/2008
Dub 408	YC11482	1/16/2008
Dub 451	YC11525	1/16/2008
Dub 466	YC11540	1/16/2008
Dub 135	YC11209	1/16/2009
Dub 140	YC11214	1/16/2009
Dub 141	YC11215	1/16/2009
Dub 142	YC11216	1/16/2009
Dub 153	YC11227	1/16/2009
Dub 154	YC11228	1/16/2009
Dub 155	YC11229	1/16/2009
Dub 156	YC11230	1/16/2009
Dub 157	YC11231	1/16/2009
Dub 158	YC11232	1/16/2009
Dub 159	YC11233	1/16/2009
Dub 179	YC11253	1/16/2009
Dub 180	YC11254	1/16/2009
Dub 190	YC11264	1/16/2009
Dub 192	YC11266	1/16/2009
Dub 193	YC11267	1/16/2009
Dub 194	YC11268	1/16/2009
Dub 195	YC11269	1/16/2009
Dub 196	YC11270	1/16/2009
Dub 197	YC11271	1/16/2009
Dub 199	YC11273	1/16/2009
Dub 200	YC11274	1/16/2009
Dub 201	YC11275	1/16/2009
Dub 202	YC11276	1/16/2009
Dub 203	YC11277	1/16/2009
Dub 217	YC11291	1/16/2009
Dub 221	YC11295	1/16/2009

Claim Label	Grant #	Current Expiry Date
Dub 225	YC11299	1/16/2009
Dub 227	YC11301	1/16/2009
Dub 228	YC11302	1/16/2009
Dub 229	YC11303	1/16/2009
Dub 230	YC11304	1/16/2009
Dub 244	YC11318	1/16/2009
Dub 245	YC11319	1/16/2009
Dub 246	YC11320	1/16/2009
Dub 247	YC11321	1/16/2009
Dub 248	YC11322	1/16/2009
Dub 249	YC11323	1/16/2009
Dub 250	YC11324	1/16/2009
Dub 251	YC11325	1/16/2009
Dub 252	YC11326	1/16/2009
Dub 253	YC11327	1/16/2009
Dub 254	YC11328	1/16/2009
Dub 255	YC11329	1/16/2009
Dub 256	YC11330	1/16/2009
Dub 261	YC11335	1/16/2009
Dub 267	YC11341	1/16/2009
Dub 268	YC11342	1/16/2009
Dub 269	YC11343	1/16/2009
Dub 270	YC11344	1/16/2009
Dub 271	YC11345	1/16/2009
Dub 272	YC11346	1/16/2009
Dub 276	YC11350	1/16/2009
Dub 277	YC11351	1/16/2009
Dub 278	YC11352	1/16/2009
Dub 279	YC11353	1/16/2009
Dub 280	YC11354	1/16/2009
Dub 289	YC11363	1/16/2009
Dub 291	YC11365	1/16/2009
Dub 292	YC11366	1/16/2009
Dub 293	YC11367	1/16/2009
Dub 294	YC11368	1/16/2009
Dub 296	YC11370	1/16/2009
Dub 300	YC11374	1/16/2009
Dub 303	YC11377	1/16/2009
Dub 304	YC11378	1/16/2009
Dub 305	YC11379	1/16/2009
Dub 306	YC11380	1/16/2009
Dub 307	YC11381	1/16/2009
Dub 308	YC11382	1/16/2009
Dub 312	YC11386	1/16/2009
Dub 313	YC11387	1/16/2009
Dub 314	YC11388	1/16/2009
Dub 315	YC11389	1/16/2009
Dub 316	YC11390	1/16/2009
Dub 317	YC11391	1/16/2009
Dub 318	YC11392	1/16/2009
Dub 319	YC11393	1/16/2009
Dub 320	YC11394	1/16/2009
Dub 325	YC11399	1/16/2009

Claim Label	Grant #	Current Expiry Date
Dub 330	YC11404	1/16/2009
Dub 331	YC11405	1/16/2009
Dub 332	YC11406	1/16/2009
Dub 333	YC11407	1/16/2009
Dub 334	YC11408	1/16/2009
Dub 335	YC11409	1/16/2009
Dub 336	YC11410	1/16/2009
Dub 337	YC11411	1/16/2009
Dub 338	YC11412	1/16/2009
Dub 340	YC11414	1/16/2009
Dub 342	YC11416	1/16/2009
Dub 344	YC11418	1/16/2009
Dub 352	YC11426	1/16/2009
Dub 365	YC11439	1/16/2009
Dub 366	YC11440	1/16/2009
Dub 367	YC11441	1/16/2009
Dub 368	YC11442	1/16/2009
Dub 370	YC11444	1/16/2009
Dub 384	YC11458	1/16/2009
Dub 397	YC11471	1/16/2009
Dub 399	YC11473	1/16/2009
Dub 400	YC11474	1/16/2009
Dub 407	YC11481	1/16/2009
Dub 418	YC11492	1/16/2009
Dub 429	YC11503	1/16/2009
Dub 430	YC11504	1/16/2009
Dub 431	YC11505	1/16/2009
Dub 432	YC11506	1/16/2009
Dub 441	YC11515	1/16/2009
Dub 443	YC11517	1/16/2009
Dub 444	YC11518	1/16/2009
Dub 446	YC11520	1/16/2009
Dub 448	YC11522	1/16/2009
Dub 449	YC11523	1/16/2009
Dub 450	YC11524	1/16/2009
Dub 452	YC11526	1/16/2009
Dub 453	YC11527	1/16/2009
Dub 454	YC11528	1/16/2009
Dub 455	YC11529	1/16/2009
Dub 456	YC11530	1/16/2009
Dub 459	YC11533	1/16/2009
Dub 460	YC11534	1/16/2009
Dub 461	YC11535	1/16/2009
Dub 462	YC11536	1/16/2009
Dub 468	YC11542	1/16/2009
Dub 470	YC11544	1/16/2009
Dub 471	YC11545	1/16/2009
Dub 472	YC11546	1/16/2009
Dub 473	YC11547	1/16/2009
Dub 475	YC11549	1/16/2009
Dub 476	YC11550	1/16/2009
Dub 477	YC11551	1/16/2009
Dub 478	YC11552	1/16/2009

Claim Label	Grant #	Current Expiry Date
Dub 479	YC11553	1/16/2009
Dub 480	YC11554	1/16/2009
Dub 1	YC11075	1/16/2010
Dub 2	YC11076	1/16/2010
Dub 3	YC11077	1/16/2010
Dub 4	YC11078	1/16/2010
Dub 5	YC11079	1/16/2010
Dub 6	YC11080	1/16/2010
Dub 7	YC11081	1/16/2010
Dub 8	YC11082	1/16/2010
Dub 9	YC11083	1/16/2010
Dub 10	YC11084	1/16/2010
Dub 11	YC11085	1/16/2010
Dub 12	YC11086	1/16/2010
Dub 13	YC11087	1/16/2010
Dub 14	YC11088	1/16/2010
Dub 15	YC11089	1/16/2010
Dub 16	YC11090	1/16/2010
Dub 17	YC11091	1/16/2010
Dub 18	YC11092	1/16/2010
Dub 19	YC11093	1/16/2010
Dub 20	YC11094	1/16/2010
Dub 21	YC11095	1/16/2010
Dub 22	YC11096	1/16/2010
Dub 23	YC11097	1/16/2010
Dub 24	YC11098	1/16/2010
Dub 25	YC11099	1/16/2010
Dub 26	YC11100	1/16/2010
Dub 27	YC11101	1/16/2010
Dub 28	YC11102	1/16/2010
Dub 29	YC11103	1/16/2010
Dub 30	YC11104	1/16/2010
Dub 31	YC11105	1/16/2010
Dub 32	YC11106	1/16/2010
Dub 33	YC11107	1/16/2010
Dub 34	YC11108	1/16/2010
Dub 35	YC11109	1/16/2010
Dub 36	YC11110	1/16/2010
Dub 37	YC11111	1/16/2010
Dub 38	YC11112	1/16/2010
Dub 39	YC11113	1/16/2010
Dub 40	YC11114	1/16/2010
Dub 41	YC11115	1/16/2010
Dub 42	YC11116	1/16/2010
Dub 43	YC11117	1/16/2010
Dub 44	YC11118	1/16/2010
Dub 45	YC11119	1/16/2010
Dub 46	YC11120	1/16/2010
Dub 47	YC11121	1/16/2010
Dub 48	YC11122	1/16/2010
Dub 49	YC11123	1/16/2010
Dub 50	YC11124	1/16/2010
Dub 51	YC11125	1/16/2010

Claim Label	Grant #	Current Expiry Date
Dub 52	YC11126	1/16/2010
Dub 53	YC11127	1/16/2010
Dub 54	YC11128	1/16/2010
Dub 55	YC11129	1/16/2010
Dub 56	YC11130	1/16/2010
Dub 57	YC11131	1/16/2010
Dub 58	YC11132	1/16/2010
Dub 59	YC11133	1/16/2010
Dub 60	YC11134	1/16/2010
Dub 61	YC11135	1/16/2010
Dub 62	YC11136	1/16/2010
Dub 63	YC11137	1/16/2010
Dub 64	YC11138	1/16/2010
Dub 65	YC11139	1/16/2010
Dub 66	YC11140	1/16/2010
Dub 67	YC11141	1/16/2010
Dub 68	YC11142	1/16/2010
Dub 69	YC11143	1/16/2010
Dub 70	YC11144	1/16/2010
Dub 71	YC11145	1/16/2010
Dub 72	YC11146	1/16/2010
Dub 73	YC11147	1/16/2010
Dub 74	YC11148	1/16/2010
Dub 75	YC11149	1/16/2010
Dub 76	YC11150	1/16/2010
Dub 77	YC11151	1/16/2010
Dub 78	YC11152	1/16/2010
Dub 79	YC11153	1/16/2010
Dub 80	YC11154	1/16/2010
Dub 81	YC11155	1/16/2010
Dub 82	YC11156	1/16/2010
Dub 83	YC11157	1/16/2010
Dub 84	YC11158	1/16/2010
Dub 85	YC11159	1/16/2010
Dub 86	YC11160	1/16/2010
Dub 87	YC11161	1/16/2010
Dub 88	YC11162	1/16/2010
Dub 89	YC11163	1/16/2010
Dub 90	YC11164	1/16/2010
Dub 91	YC11165	1/16/2010
Dub 92	YC11166	1/16/2010
Dub 93	YC11167	1/16/2010
Dub 94	YC11168	1/16/2010
Dub 95	YC11169	1/16/2010
Dub 96	YC11170	1/16/2010
Dub 97	YC11171	1/16/2010
Dub 98	YC11172	1/16/2010
Dub 99	YC11173	1/16/2010
Dub 100	YC11174	1/16/2010
Dub 101	YC11175	1/16/2010
Dub 102	YC11176	1/16/2010
Dub 103	YC11177	1/16/2010
Dub 104	YC11178	1/16/2010

Claim Label	Grant #	Current Expiry Date
Dub 105	YC11179	1/16/2010
Dub 106	YC11180	1/16/2010
Dub 107	YC11181	1/16/2010
Dub 108	YC11182	1/16/2010
Dub 109	YC11183	1/16/2010
Dub 110	YC11184	1/16/2010
Dub 111	YC11185	1/16/2010
Dub 112	YC11186	1/16/2010
Dub 113	YC11187	1/16/2010
Dub 114	YC11188	1/16/2010
Dub 115	YC11189	1/16/2010
Dub 116	YC11190	1/16/2010
Dub 117	YC11191	1/16/2010
Dub 118	YC11192	1/16/2010
Dub 119	YC11193	1/16/2010
Dub 120	YC11194	1/16/2010
Dub 121	YC11195	1/16/2010
Dub 122	YC11196	1/16/2010
Dub 123	YC11197	1/16/2010
Dub 124	YC11198	1/16/2010
Dub 125	YC11199	1/16/2010
Dub 126	YC11200	1/16/2010
Dub 127	YC11201	1/16/2010
Dub 128	YC11202	1/16/2010
Dub 129	YC11203	1/16/2010
Dub 130	YC11204	1/16/2010
Dub 131	YC11205	1/16/2010
Dub 132	YC11206	1/16/2010
Dub 133	YC11207	1/16/2010
Dub 134	YC11208	1/16/2010
Dub 143	YC11217	1/16/2010
Dub 144	YC11218	1/16/2010
Dub 145	YC11219	1/16/2010
Dub 146	YC11220	1/16/2010
Dub 147	YC11221	1/16/2010
Dub 148	YC11222	1/16/2010
Dub 149	YC11223	1/16/2010
Dub 150	YC11224	1/16/2010
Dub 151	YC11225	1/16/2010
Dub 152	YC11226	1/16/2010
Dub 160	YC11234	1/16/2010
Dub 161	YC11235	1/16/2010
Dub 162	YC11236	1/16/2010
Dub 163	YC11237	1/16/2010
Dub 164	YC11238	1/16/2010
Dub 165	YC11239	1/16/2010
Dub 166	YC11240	1/16/2010
Dub 167	YC11241	1/16/2010
Dub 168	YC11242	1/16/2010
Dub 181	YC11255	1/16/2010
Dub 182	YC11256	1/16/2010
Dub 183	YC11257	1/16/2010
Dub 184	YC11258	1/16/2010

Claim Label	Grant #	Current Expiry Date
Dub 185	YC11259	1/16/2010
Dub 186	YC11260	1/16/2010
Dub 187	YC11261	1/16/2010
Dub 188	YC11262	1/16/2010
Dub 189	YC11263	1/16/2010
Dub 191	YC11265	1/16/2010
Dub 198	YC11272	1/16/2010
Dub 209	YC11283	1/16/2010
Dub 210	YC11284	1/16/2010
Dub 211	YC11285	1/16/2010
Dub 212	YC11286	1/16/2010
Dub 213	YC11287	1/16/2010
Dub 214	YC11288	1/16/2010
Dub 215	YC11289	1/16/2010
Dub 216	YC11290	1/16/2010
Dub 218	YC11292	1/16/2010
Dub 220	YC11294	1/16/2010
Dub 222	YC11296	1/16/2010
Dub 224	YC11298	1/16/2010
Dub 226	YC11300	1/16/2010
Dub 233	YC11307	1/16/2010
Dub 234	YC11308	1/16/2010
Dub 235	YC11309	1/16/2010
Dub 236	YC11310	1/16/2010
Dub 237	YC11311	1/16/2010
Dub 238	YC11312	1/16/2010
Dub 239	YC11313	1/16/2010
Dub 240	YC11314	1/16/2010
Dub 241	YC11315	1/16/2010
Dub 242	YC11316	1/16/2010
Dub 243	YC11317	1/16/2010
Dub 273	YC11347	1/16/2010
Dub 274	YC11348	1/16/2010
Dub 275	YC11349	1/16/2010
Dub 297	YC11371	1/16/2010
Dub 298	YC11372	1/16/2010
Dub 299	YC11373	1/16/2010
Dub 301	YC11375	1/16/2010
Dub 302	YC11376	1/16/2010
Dub 339	YC11413	1/16/2010
Dub 341	YC11415	1/16/2010
Dub 343	YC11417	1/16/2010
Dub 345	YC11419	1/16/2010
Dub 347	YC11421	1/16/2010
Dub 349	YC11423	1/16/2010
Dub 351	YC11425	1/16/2010
Dub 353	YC11427	1/16/2010
Dub 355	YC11429	1/16/2010
Dub 375	YC11449	1/16/2010
Dub 376	YC11450	1/16/2010
Dub 377	YC11451	1/16/2010
Dub 378	YC11452	1/16/2010
Dub 379	YC11453	1/16/2010

Claim Label	Grant #	Current Expiry Date
Dub 380	YC11454	1/16/2010
Dub 381	YC11455	1/16/2010
Dub 382	YC11456	1/16/2010
Dub 383	YC11457	1/16/2010
Dub 385	YC11459	1/16/2010
Dub 386	YC11460	1/16/2010
Dub 387	YC11461	1/16/2010
Dub 388	YC11462	1/16/2010
Dub 389	YC11463	1/16/2010
Dub 390	YC11464	1/16/2010
Dub 409	YC11483	1/16/2010
Dub 410	YC11484	1/16/2010
Dub 411	YC11485	1/16/2010
Dub 412	YC11486	1/16/2010
Dub 413	YC11487	1/16/2010
Dub 414	YC11488	1/16/2010
Dub 415	YC11489	1/16/2010
Dub 416	YC11490	1/16/2010
Dub 417	YC11491	1/16/2010
Dub 419	YC11493	1/16/2010
Dub 420	YC11494	1/16/2010
Dub 421	YC11495	1/16/2010
Dub 422	YC11496	1/16/2010
Dub 423	YC11497	1/16/2010
Dub 424	YC11498	1/16/2010
Dub 425	YC11499	1/16/2010
Dub 426	YC11500	1/16/2010
Dub 427	YC11501	1/16/2010
Dub 428	YC11502	1/16/2010
Dub 433	YC11507	1/16/2010
Dub 434	YC11508	1/16/2010
Dub 435	YC11509	1/16/2010
Dub 436	YC11510	1/16/2010
Dub 437	YC11511	1/16/2010
Dub 438	YC11512	1/16/2010
Dub 439	YC11513	1/16/2010
Dub 440	YC11514	1/16/2010
Dub 442	YC11516	1/16/2010
Dub 445	YC11519	1/16/2010
Dub 447	YC11521	1/16/2010
Dub 457	YC11531	1/16/2010
Dub 458	YC11532	1/16/2010
Dub 463	YC11537	1/16/2010
Dub 464	YC11538	1/16/2010
Dub 465	YC11539	1/16/2010
Dub 467	YC11541	1/16/2010
Dub 469	YC11543	1/16/2010
Dub 474	YC11548	1/16/2010
Lynx 57	YC11555	1/16/2010
Lynx 1	YC10463	1/16/2014
Lynx 2	YC10464	1/16/2014
Lynx 3	YC10465	1/16/2014
Lynx 4	YC10466	1/16/2014

Claim Label	Grant #	Current Expiry Date
Lynx 5	YC10467	1/16/2014
Lynx 6	YC10468	1/16/2014
Lynx 7	YC10469	1/16/2014
Lynx 8	YC10470	1/16/2014
Lynx 9	YC10471	1/16/2014
Lynx 10	YC10472	1/16/2014
Lynx 11	YC10473	1/16/2014
Lynx 12	YC10474	1/16/2014
Lynx 13	YC10475	1/16/2014
Lynx 15	YC10477	1/16/2014
Lynx 16	YC10478	1/16/2014
Lynx 17	YC10479	1/16/2014
Lynx 18	YC10480	1/16/2014
Lynx 19	YC10481	1/16/2014
Lynx 20	YC10482	1/16/2014
Lynx 21	YC10483	1/16/2014
Lynx 22	YC10484	1/16/2014
Lynx 23	YC10485	1/16/2014
Lynx 27	YC10489	1/16/2014
Lynx 28	YC10490	1/16/2014
Lynx 29	YC10491	1/16/2014
Lynx 30	YC10492	1/16/2014
Lynx 31	YC10493	1/16/2014
Lynx 32	YC10494	1/16/2014
Lynx 42	YC10504	1/16/2014
Lynx 44	YC10506	1/16/2014
Lynx 45	YC10507	1/16/2014
Lynx 14	YC10476	1/16/2015
Lynx 24	YC10486	1/16/2015
Lynx 25	YC10487	1/16/2015
Lynx 26	YC10488	1/16/2015
Lynx 33	YC10495	1/16/2015
Lynx 34	YC10496	1/16/2015
Lynx 35	YC10497	1/16/2015
Lynx 36	YC10498	1/16/2015
Lynx 37	YC10499	1/16/2015
Lynx 38	YC10500	1/16/2015
Lynx 39	YC10501	1/16/2015
Lynx 40	YC10502	1/16/2015
Lynx 41	YC10503	1/16/2015
Lynx 43	YC10505	1/16/2015
Lynx 46	YC10508	1/16/2015
Lynx 47	YC10509	1/16/2015
Lynx 48	YC10510	1/16/2015
Lynx 49	YC10511	1/16/2015
Lynx 50	YC10512	1/16/2015
Lynx 51	YC10513	1/16/2015
Lynx 55	YC10517	1/16/2015
Lynx 52	YC10514	1/16/2016
Lynx 53	YC10515	1/16/2016
Lynx 54	YC10516	1/16/2016
Lynx 56	YC10518	1/16/2016
Jan 1	YB65585	1/16/2018

Claim Label	Grant #	Current Expiry Date
Jan 2	YB65586	1/16/2018
Jan 3	YB65587	1/16/2018
Jan 4	YB65588	1/16/2018
Dave 13	YA17814	1/31/2011
Dave 14	YA17815	1/31/2011
Dave 15	YA17816	1/31/2011
Dave 16	YA17817	1/31/2011
Dave 25	YA42970	1/31/2011
Dave 27	YA42972	1/31/2011
Dave 28	YA42973	1/31/2011
R & D 9	YA01401	1/31/2011
R & D 11	YA01403	1/31/2011
R & D 13	YA01405	1/31/2011
Dub 1390	YC38686	11/17/2005
Dub 1391	YC38687	11/17/2005
Dub 1392	YC38688	11/17/2005
Dub 1393	YC38689	11/17/2005
Len 3	YC02732	5/15/2015
Len 5	YC02733	5/15/2015
Len 7	YC02734	5/15/2015
Len 9	YC02735	5/15/2015
Len 25	YC02749	5/15/2015
Len 27	YC02750	5/15/2015
Len 29	YC02751	5/15/2015
Len 31	YC02752	5/15/2015
Len 32	YC02753	5/15/2015
Len 1	YC02730	5/15/2017
Len 2	YC02731	5/15/2017
Len 11	YC02736	5/15/2017
Len 12	YC02737	5/15/2017
Len 13	YC02738	5/15/2017
Len 14	YC02739	5/15/2017
Len 15	YC02740	5/15/2017
Len 16	YC02741	5/15/2017
Len 17	YC02742	5/15/2017
Len 18	YC02743	5/15/2017
Len 19	YC02744	5/15/2017
Len 20	YC02745	5/15/2017
Len 21	YC02746	5/15/2017
Len 22	YC02747	5/15/2017
Len 23	YC02748	5/15/2017
Len 4	YA30524	5/15/2018
Len 6	YA30526	5/15/2018
Len 8	YA30528	5/15/2018
Len 10	YA30530	5/15/2018
Len 24	YA30544	5/15/2018
Len 26	YA30546	5/15/2018
Len 28	YA30548	5/15/2018
Len 30	YA30550	5/15/2018

APPENDIX C

Figure 3

Figure 3: Dublin Gulch Drill Collar Plan Map

CAMP

458000 mE | 458500 mE | 459000 mE | 459500 mE | 460000 mE | 460500 mE | 461000 mE | 461500 mE

7100750 mN | 7100250 mN | 7099750 mN | 7099250 mN | 7098750 mN

STEINER ZONE

EAGLE ZONE

DG05-294C | DG05-296C | DG05-305C | DG05-284C | DG05-298C | DG05-286C | DG05-282C | DG05-280C | DG05-288C | DG05-292C | DG05-293C | DG05-291C | DG05-289C | DG05-299C | DG05-297C | DG05-278C | DG05-277C | DG05-279C | DG05-281C | DG05-276C | DG05-309C | DG05-287C | DG05-300C | DG05-301C | DG05-295C | DG05-283C | DG05-285C | DG05-303C | DG05-302C | DG05-306C | DG05-304C | DG05-307C | DG05-308C

95-151C | 96-242C | 96-241C | 96-243C | 95-152C | 96-262R | 92-046R | 96-260R | 96-238C | 96-261R | 96-240C | 92-027R | 95-122C | 96-259R | 92-028R | 92-019R | 96-198C | 96-237C | 92-024R | 93-063R | 95-121C | 96-239C | 92-022R | 96-235C | 92-040R | 92-026R | 93-070R | 92-049R | 93-071R | 92-048R | 92-032R | 93-067R | 91-010C | 92-041R | 92-018R | 96-210C | 92-039R | 92-052R | 95-120C | 92-025R | 92-045R | 92-044R | 92-043R | 96-156C | 96-159C | 96-172R | 96-169R | 91-008C | 96-192C | 91-014C | 96-190R | 96-167R | 95-154R | 96-189R | 92-042R | TR460475E | 95-088R | 91-007C | 92-060R | 91-011C | 95-089R | 95-083R | 96-264R | 96-161C | 95-075C | 93-065R | 95-077C | 96-266R | 95-105C | 96-269R | 93-072R | 96-164R | 96-163R | 95-132R | 95-098R | 96-179R | 92-051R | 95-135R | 95-133R | 96-155C | 92-056R | 91-006C | 91-009C | 91-005C | 95-127R | 95-097R | 95-092R | 96-180R | 95-086R | 92-054R | 95-104C | 92-061R | 96-165R | 91-004C | 95-094R | 91-003C | 95-200C | 92-023R | 96-207C | 95-137C | 95-079C | 96-153C | 92-059R | 95-093R | 95-076C | 95-095R | 91-002C | 91-001C | 92-031R | TR459075E | 96-235C | 96-213C | 95-234C | 96-212C | 96-211C

92-034R | 86-2 C | 86-1 C

N

LEGEND

DG05-XXXC 2005 DRILL HOLES | HISTORICAL DRILL HOLES | WATERCOURSE | CONTOUR

StrataGold Corporation

094876

Date:10/11/2005
Author: DH
Office: Vancouver
Figure: 3
Scale: 1:5000

Dublin Gulch
Drill Collar Plan Map

Projection: UTM Zone 8 (NAD 27 for Canada)

0 75 150 300
metres

094876

APPENDIX D

Dublin Gulch 2005 Return Sample Details

And ALS Chemex Assay Certificates

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-276C	15.24	16.76	1.52	290101	Return/Silt	GND	VA05045076
DG05-276C	16.76	18.29	1.53	290102	Return/Silt	GND	VA05045076
DG05-276C	18.29	19.81	1.52	290103	Return/Silt	GND	VA05045076
DG05-276C	19.81	21.34	1.53	209104	Return/Silt	GND	VA05045076
DG05-276C	21.34	22.86	1.52	209105	Return/Silt	GND	VA05045076
DG05-276C	22.86	24.38	1.52	290106	Return/Silt	GND	VA05045076
DG05-276C	24.38	25.91	1.53	290107	Return/Silt	GND	VA05045076
DG05-276C	25.91	27.43	1.52	290108	Return/Silt	GND	VA05045076
DG05-276C	38.1	39.62	1.52	290109	Return/Silt	GND	VA05045076
DG05-276C	39.62	41.16	1.54	290110	Return/Silt	GND	VA05045076
DG05-277C	18.21	19.81	1.6	290111	Return/Silt	GND	VA05045076
DG05-277C	19.81	21.34	1.53	290112	Return/Silt	GND	VA05045076
DG05-277C	21.34	22.86	1.52	290113	Return/Silt	GND	VA05045076
DG05-278C	No Return after casing						
DG05-279C							
DG05-280C	22.86	24.38	1.52	290114	Return/Silt	GND	VA05047184
DG05-280C	24.38	25.91	1.53	290115	Return/Silt	GND	VA05047184
DG05-280C	25.91	27.43	1.52	290116	Return/Silt	GND	VA05047184
DG05-280C	27.43	28.96	1.53	290117	Return/Silt	GND	VA05047184
DG05-280C	28.96	30.48	1.52	290118	Return/Silt	GND	VA05047184
DG05-280C	30.48	32.00	1.52	290119	Return/Silt	GND	VA05047184
DG05-280C	32.00	33.53	1.53	290120	Return/Silt	GND	VA05047184
DG05-280C	33.53	35.05	1.52	290121	Return/Silt	GND	VA05047184
DG05-280C	35.05	36.58	1.53	290122	Return/Silt	GND	VA05047184
DG05-280C	36.58	38.10	1.52	290123	Return/Silt	GND	VA05047184
DG05-280C	38.10	39.62	1.52	290124	Return/Silt	GND	VA05047184
DG05-280C	39.62	41.15	1.53	290125	Return/Silt	GND	VA05047184
DG05-280C	41.15	42.67	1.52	290126	Return/Silt	GND	VA05047184
DG05-280C	42.67	44.20	1.53	290127	Return/Silt	GND	VA05047184
DG05-280C	44.20	45.72	1.52	290128	Return/Silt	GND	VA05047184
DG05-280C	45.72	47.24	1.52	290129	Return/Silt	GND	VA05047184
DG05-280C	47.24	48.77	1.53	290130	Return/Silt	GND	VA05047184
DG05-280C	48.77	50.29	1.52	290131	Return/Silt	GND	VA05047184
DG05-280C	50.29	51.82	1.53	290132	Return/Silt	GND	VA05047184
DG05-280C	51.82	53.34	1.52	290133	Return/Silt	GND	VA05047184
DG05-280C	53.34	54.86	1.52	290134	Return/Silt	GND	VA05047184
DG05-280C	54.86	56.39	1.53	290135	Return/Silt	GND	VA05047184
DG05-280C	56.39	57.91	1.52	290136	Return/Silt	GND	VA05047184
DG05-280C	57.91	59.44	1.53	290137	Return/Silt	GND	VA05047184
DG05-280C	59.44	60.96	1.52	290138	Return/Silt	GND	VA05047184
DG05-280C	60.96	62.48	1.52	290139	Return/Silt	GND	VA05047184
DG05-280C	62.48	64.01	1.53	290140	Return/Silt	GND	VA05047184
DG05-280C	64.01	65.53	1.52	290141	Return/Silt	GND	VA05047184
DG05-280C	65.53	67.06	1.53	290142	Return/Silt	GND	VA05047184
DG05-280C	67.06	68.58	1.52	290143	Return/Silt	GND	VA05047184
DG05-280C	68.58	70.10	1.52	290144	Return/Silt	GND	VA05047184
DG05-280C	70.10	71.63	1.53	290145	Return/Silt	GND	VA05047184
DG05-280C	71.63	73.15	1.52	290146	Return/Silt	GND	VA05047184
DG05-280C	73.15	74.68	1.53	290147	Return/Silt	GND	VA05047184
DG05-280C	74.68	76.20	1.52	290148	Return/Silt	GND	VA05047184
DG05-280C	76.20	77.72	1.52	290149	Return/Silt	GND	VA05047184
DG05-280C	77.72	79.25	1.53	290150	Return/Silt	GND	VA05047184
DG05-280C	79.25	80.77	1.52	290151	Return/Silt	GND	VA05047184
DG05-280C	80.77	82.30	1.53	290152	Return/Silt	GND	VA05047184
DG05-280C	94.49	96.01	1.52	290153	Return/Silt	GND	VA05047184
DG05-280C	96.01	97.54	1.53	290154	Return/Silt	GND	VA05047184
DG05-280C	97.54	99.06	1.52	290155	Return/Silt	GND	VA05047184
DG05-280C	99.06	100.58	1.52	290156	Return/Silt	GND	VA05047184
DG05-280C	100.58	102.11	1.53	290157	Return/Silt	GND	VA05047184

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-280C	102.11	103.63	1.52	290158	Return/Silt	GND	VA05047184
DG05-280C	103.63	105.16	1.53	290159	Return/Silt	GND	VA05047826
DG05-280C	105.16	106.68	1.52	290160	Return/Silt	GND	VA05047826
DG05-280C	106.68	108.20	1.52	290161	Return/Silt	GND	VA05047826
DG05-280C	108.20	109.73	1.53	290162	Return/Silt	GND	VA05047826
DG05-280C	109.73	111.25	1.52	290163	Return/Silt	GND	VA05047826
DG05-280C	111.25	112.78	1.53	290164	Return/Silt	GND	VA05047826
DG05-280C	112.78	114.30	1.52	290165	Return/Silt	GND	VA05047826
DG05-280C	114.30	115.87	1.57	290166	Return/Silt	GND	VA05047826
DG05-280C	115.87	117.35	1.48	290167	Return/Silt	GND	VA05047826
DG05-280C	117.35	118.87	1.52	290168	Return/Silt	GND	VA05047826
DG05-280C	118.87	120.40	1.53	290169	Return/Silt	GND	VA05047826
DG05-280C	120.40	121.92	1.52	290170	Return/Silt	GND	VA05047826
DG05-280C	121.92	123.44	1.52	290171	Return/Silt	GND	VA05047826
DG05-280C	123.44	124.97	1.53	290172	Return/Silt	GND	VA05047826
DG05-280C	124.97	126.49	1.52	290173	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290174	Return/Silt	GND	VA05047826
DG05-280C	129.54	131.06	1.52	290175	Return/Silt	GND	VA05047826
DG05-280C	131.06	132.59	1.53	290176	Return/Silt	GND	VA05047826
DG05-280C	132.59	134.11	1.52	290177	Return/Silt	GND	VA05047826
DG05-280C	134.11	135.64	1.53	290178	Return/Silt	GND	VA05047826
DG05-280C	135.64	137.16	1.52	290179	Return/Silt	GND	VA05047826
DG05-280C	137.16	138.68	1.52	290180	Return/Silt	GND	VA05047826
DG05-280C	138.68	140.21	1.53	290181	Return/Silt	GND	VA05047826
DG05-280C	140.21	141.73	1.52	290182	Return/Silt	GND	VA05047826
DG05-280C	141.73	143.26	1.53	290183	Return/Silt	GND	VA05047826
DG05-280C	143.26	144.78	1.52	290184	Return/Silt	GND	VA05047826
DG05-280C	144.78	146.30	1.52	290185	Return/Silt	GND	VA05047826
DG05-280C	146.30	147.83	1.53	290186	Return/Silt	GND	VA05047826
DG05-280C	147.83	149.35	1.52	290187	Return/Silt	GND	VA05047826
DG05-280C	149.35	150.88	1.53	290188	Return/Silt	GND	VA05047826
DG05-280C	150.88	152.40	1.52	290189	Return/Silt	GND	VA05047826
DG05-280C	192.02	193.55	1.53	290190	Return/Silt	GND	VA05047826
DG05-280C	193.55	195.07	1.52	290191	Return/Silt	GND	VA05047826
DG05-280C	195.07	196.60	1.53	290192	Return/Silt	GND	VA05047826
DG05-280C	196.60	198.12	1.52	290193	Return/Silt	GND	VA05047826
DG05-280C	198.12	199.64	1.52	290194	Return/Silt	GND	VA05047826
DG05-280C	199.64	201.17	1.53	290195	Return/Silt	GND	VA05047826
DG05-280C	201.17	202.69	1.52	290196	Return/Silt	GND	VA05047826
DG05-280C	202.69	204.22	1.53	290197	Return/Silt	GND	VA05047826
DG05-280C	204.22	205.74	1.52	290198	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290199	Return/Silt	GND	VA05048596
DG05-281C	25.91	27.43	1.52	290200	Return/Silt	GND	VA05048596
DG05-281C	27.43	28.96	1.53	290201	Return/Silt	GND	VA05048596
DG05-281C	28.96	30.48	1.52	290202	Return/Silt	GND	VA05048596
DG05-281C	30.48	32.00	1.52	290203	Return/Silt	GND	VA05048596
DG05-281C	32.00	33.53	1.53	290204	Return/Silt	GND	VA05048596
DG05-281C	33.53	35.06	1.53	290205	Return/Silt	GND	VA05048596
DG05-281C	35.06	36.58	1.52	290206	Return/Silt	GND	VA05048596
DG05-281C	36.58	38.10	1.52	290207	Return/Silt	GND	VA05048596
DG05-281C	38.10	39.62	1.52	290208	Return/Silt	GND	VA05048596
DG05-281C	39.62	41.15	1.53	290209	Return/Silt	GND	VA05048596
DG05-281C	41.15	42.67	1.52	290210	Return/Silt	GND	VA05048596
DG05-281C	42.67	44.20	1.53	290211	Return/Silt	GND	VA05048596
DG05-281C	44.20	45.72	1.52	290212	Return/Silt	GND	VA05048596
DG05-281C	45.72	47.24	1.52	290213	Return/Silt	GND	VA05048596
DG05-281C	47.24	48.77	1.53	290214	Return/Silt	GND	VA05048596
DG05-281C	48.77	50.29	1.52	290215	Return/Silt	GND	VA05048596
DG05-281C	50.29	51.82	1.53	290216	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-281C	51.82	53.34	1.52	290217	Return/Silt	GND	VA05048596
DG05-281C	53.34	54.86	1.52	290218	Return/Silt	GND	VA05048596
DG05-281C	54.86	56.39	1.53	290219	Return/Silt	GND	VA05048596
DG05-281C	56.39	57.91	1.52	290220	Return/Silt	GND	VA05048596
DG05-281C	57.91	59.44	1.53	290221	Return/Silt	GND	VA05048596
DG05-281C	59.44	60.96	1.52	290222	Return/Silt	GND	VA05048596
DG05-281C	60.96	62.48	1.52	290223	Return/Silt	GND	VA05048596
DG05-281C	62.48	64.01	1.53	290224	Return/Silt	GND	VA05048596
DG05-281C	64.01	65.53	1.52	290225	Return/Silt	GND	VA05048596
DG05-281C	65.53	67.06	1.53	290226	Return/Silt	GND	VA05048596
DG05-281C	67.06	68.58	1.52	290227	Return/Silt	GND	VA05048596
DG05-281C	68.58	70.10	1.52	290228	Return/Silt	GND	VA05048596
DG05-281C	70.10	71.63	1.53	290229	Return/Silt	GND	VA05048596
DG05-281C	71.63	74.68	3.05	290230	Return/Silt	GND	VA05048596
DG05-281C	74.68	76.20	1.52	290231	Return/Silt	GND	VA05048596
DG05-281C	76.20	77.72	1.52	290232	Return/Silt	GND	VA05048596
DG05-281C	77.72	79.25	1.53	290233	Return/Silt	GND	VA05048596
DG05-281C	79.25	80.77	1.52	290234	Return/Silt	GND	VA05048596
DG05-281C	80.77	82.30	1.53	290235	Return/Silt	GND	VA05048596
DG05-281C	82.30	83.82	1.52	290236	Return/Silt	GND	VA05048596
DG05-281C	83.82	85.39	1.57	290237	Return/Silt	GND	VA05048596
DG05-281C	85.39	86.87	1.48	290238	Return/Silt	GND	VA05048596
DG05-281C	86.87	88.39	1.52	290239	Return/Silt	GND	VA05048596
DG05-281C	88.39	89.92	1.53	290240	Return/Silt	GND	VA05048596
DG05-281C	89.92	91.44	1.52	290241	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290242	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290243	Return/Silt	GND	VA05048596
DG05-281C	92.96	94.49	1.53	290244	Return/Silt	GND	VA05048596
DG05-281C	94.49	96.01	1.52	290245	Return/Silt	GND	VA05048596
DG05-281C	96.01	97.54	1.53	290246	Return/Silt	GND	VA05048596
DG05-281C	97.54	99.06	1.52	290247	Return/Silt	GND	VA05048596
DG05-281C	99.06	100.58	1.52	290248	Return/Silt	GND	VA05048596
DG05-281C	100.58	102.11	1.53	290249	Return/Silt	GND	VA05048596
DG05-281C	102.11	103.63	1.52	290250	Return/Silt	GND	VA05048596
DG05-281C	103.63	105.16	1.53	290251	Return/Silt	GND	VA05048596
DG05-281C	105.16	106.68	1.52	290252	Return/Silt	GND	VA05048596
DG05-281C	106.68	108.20	1.52	290253	Return/Silt	GND	VA05048596
DG05-281C	108.20	109.73	1.53	290254	Return/Silt	GND	VA05048596
DG05-281C	109.73	111.25	1.52	290255	Return/Silt	GND	VA05048596
DG05-281C	111.25	112.78	1.53	290256	Return/Silt	GND	VA05048596
DG05-281C	112.78	114.30	1.52	290257	Return/Silt	GND	VA05048596
DG05-281C	114.30	115.82	1.52	290258	Return/Silt	GND	VA05048596
DG05-281C	115.82	117.35	1.53	290259	Return/Silt	GND	VA05048596
DG05-281C	117.35	118.87	1.52	290260	Return/Silt	GND	VA05048596
DG05-281C	118.87	120.40	1.53	290261	Return/Silt	GND	VA05048596
DG05-281C	120.40	121.92	1.52	290262	Return/Silt	GND	VA05048596
DG05-281C	121.92	123.44	1.52	290263	Return/Silt	GND	VA05048596
DG05-281C	123.44	124.97	1.53	290264	Return/Silt	GND	VA05048596
DG05-281C	124.97	126.49	1.52	290265	Return/Silt	GND	VA05048596
DG05-282C	15.24	16.76	1.52	290266	Return/Silt	GND	VA05048596
DG05-282C	30.48	32.00	1.52	290267	Return/Silt	GND	VA05048596
DG05-282C	32.00	33.53	1.53	290268	Return/Silt	GND	VA05048596
DG05-282C	33.53	35.05	1.52	290269	Return/Silt	GND	VA05048596
DG05-282C	35.05	36.58	1.53	290270	Return/Silt	GND	VA05048596
DG05-282C	36.58	38.10	1.52	290271	Return/Silt	GND	VA05048596
DG05-282C	38.10	39.66	1.56	290272	Return/Silt	GND	VA05048596
DG05-282C	39.66	41.15	1.49	290273	Return/Silt	GND	VA05048596
DG05-282C	41.15	42.67	1.52	290274	Return/Silt	GND	VA05048596
DG05-282C	42.67	44.20	1.53	290275	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	86.87	88.39	1.52	290276	Return/Silt	GND	VA05048596
DG05-282C	88.39	89.92	1.53	290277	Return/Silt	GND	VA05048596
DG05-282C	89.92	91.44	1.52	290278	Return/Silt	GND	VA05048596
DG05-282C	91.44	92.96	1.52	290279	Return/Silt	GND	VA05048596
DG05-282C	92.96	94.49	1.53	290280	Return/Silt	GND	VA05048596
DG05-282C	94.49	96.01	1.52	290281	Return/Silt	GND	VA05048596
DG05-282C	96.01	97.54	1.53	290282	Return/Silt	GND	VA05048596
DG05-282C	97.54	99.06	1.52	290283	Return/Silt	GND	VA05048596
DG05-282C	99.06	100.58	1.52	290284	Return/Silt	GND	VA05048596
DG05-282C	100.58	102.11	1.53	290285	Return/Silt	GND	VA05048596
DG05-282C	102.11	103.63	1.52	290286	Return/Silt	GND	VA05048596
DG05-282C	103.63	105.16	1.53	290287	Return/Silt	GND	VA05048596
DG05-282C	105.16	106.68	1.52	290288	Return/Silt	GND	VA05048596
DG05-282C	106.68	108.20	1.52	290289	Return/Silt	GND	VA05048596
DG05-282C	108.20	109.73	1.53	290290	Return/Silt	GND	VA05048596
DG05-282C	114.30	115.82	1.52	290291	Return/Silt	GND	VA05048596
DG05-282C	115.82	117.35	1.53	290292	Return/Silt	GND	VA05048596
DG05-282C	117.35	118.87	1.52	290293	Return/Silt	GND	VA05048596
DG05-282C	118.87	120.40	1.53	290294	Return/Silt	GND	VA05048596
DG05-282C	120.40	121.92	1.52	290295	Return/Silt	GND	VA05048596
DG05-282C	121.92	123.44	1.52	290296	Return/Silt	GND	VA05048596
DG05-282C	123.44	124.97	1.53	290297	Return/Silt	GND	VA05048596
DG05-282C	124.97	126.49	1.52	290298	Return/Silt	GND	VA05048596
DG05-282C	126.49	128.02	1.53	290299	Return/Silt	GND	VA05048596
DG05-282C	128.02	129.54	1.52	290300	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290301	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290302	Return/Silt	GND	VA05048596
DG05-282C	131.06	132.59	1.53	290303	Return/Silt	GND	VA05048596
DG05-282C	132.59	134.11	1.52	290304	Return/Silt	GND	VA05048596
DG05-282C	134.11	135.64	1.53	290305	Return/Silt	GND	VA05048596
DG05-282C	135.64	137.16	1.52	290306	Return/Silt	GND	VA05048596
DG05-282C	137.16	138.68	1.52	290307	Return/Silt	GND	VA05048596
DG05-282C	138.68	140.21	1.53	290308	Return/Silt	GND	VA05048596
DG05-282C	140.21	141.73	1.52	290309	Return/Silt	GND	VA05048596
DG05-282C	141.73	143.26	1.53	290310	Return/Silt	GND	VA05048596
DG05-282C	144.78	146.30	1.52	290311	Return/Silt	GND	VA05048596
DG05-282C	146.30	147.83	1.53	290312	Return/Silt	GND	VA05048596
DG05-282C	147.83	149.35	1.52	290313	Return/Silt	GND	VA05048596
DG05-282C	149.35	150.88	1.53	290314	Return/Silt	GND	VA05048596
DG05-282C	150.88	152.40	1.52	290315	Return/Silt	GND	VA05048596
DG05-282C	152.40	153.92	1.52	290316	Return/Silt	GND	VA05048596
DG05-282C	153.92	155.45	1.53	290317	Return/Silt	GND	VA05048596
DG05-282C	155.45	156.97	1.52	290318	Return/Silt	GND	VA05048596
DG05-282C	156.97	158.50	1.53	290319	Return/Silt	GND	VA05048596
DG05-282C	158.50	160.02	1.52	290320	Return/Silt	GND	VA05048596
DG05-282C	160.02	161.54	1.52	290321	Return/Silt	GND	VA05048596
DG05-282C	161.54	163.07	1.53	290322	Return/Silt	GND	VA05048596
DG05-282C	163.07	164.59	1.52	290323	Return/Silt	GND	VA05048596
DG05-282C	164.59	166.12	1.53	290324	Return/Silt	GND	VA05048596
DG05-282C	166.12	167.64	1.52	290325	Return/Silt	GND	VA05048596
DG05-282C	111.25	112.78	1.53	290326	Return/Silt	GND	VA05049478
DG05-280C	22.86	24.38	1.52	290327	Return/Silt	GND	VA05049478
DG05-282C	109.73	111.25	1.52	290328	Return/Silt	GND	VA05049478
DG05-282C	112.78	114.30	1.52	290329	Return/Silt	GND	VA05049478
DG05-282C	196.60	198.12	1.52	290330	Return/Silt	MSED	VA05049478
DG05-282C	198.12	199.64	1.52	290331	Return/Silt	MSED	VA05049478
DG05-282C	199.64	201.17	1.52	290332	Return/Silt	MSED	VA05049478
DG05-282C	201.17	202.69	1.53	290333	Return/Silt	MSED	VA05049478
DG05-282C	202.69	204.22	1.52	290334	Return/Silt	MSED	VA05049478

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	204.22	205.74	1.53	290335	Return/Silt	MSED	VA05049478
DG05-282C	205.74	207.26	1.52	290336	Return/Silt	MSED	VA05049478
DG05-282C	242.32	243.84	1.52	290337	Return/Silt	MSED	VA05049478
DG05-282C	245.36	246.89	1.52	290338	Return/Silt	MSED	VA05049478
DG05-282C	246.89	248.41	1.53	290339	Return/Silt	MSED	VA05049478
DG05-282C	248.41	249.94	1.52	290340	Return/Silt	MSED	VA05049478
DG05-282C	249.94	251.46	1.53	290341	Return/Silt	MSED	VA05049478
DG05-282C	251.46	252.98	1.52	290342	Return/Silt	MSED	VA05049478
DG05-283C	24.38	25.91	1.53	B290343	Return/Silt	GND	VA05053955
DG05-283C	25.91	27.43	1.52	B290344	Return/Silt	GND	VA05053955
DG05-283C	27.43	28.96	1.53	B290345	Return/Silt	GND	VA05053955
DG05-283C	28.96	30.48	1.52	B290346	Return/Silt	GND	VA05053955
DG05-283C	30.48	32.00	1.52	B290347	Return/Silt	GND	VA05053955
DG05-283C	32.00	33.53	1.53	B290348	Return/Silt	GND	VA05053955
DG05-283C	33.53	35.05	1.52	B290349	Return/Silt	GND	VA05053955
DG05-283C	35.05	36.58	1.53	B290350	Return/Silt	GND	VA05053955
DG05-283C	36.58	38.10	1.52	B290351	Return/Silt	GND	VA05053955
DG05-283C	38.10	39.62	1.52	B290352	Return/Silt	GND	VA05053955
DG05-283C	39.62	41.15	1.53	B290353	Return/Silt	GND	VA05053955
DG05-283C	41.15	42.67	1.52	B290354	Return/Silt	GND	VA05053955
DG05-283C	42.67	44.20	1.53	B290355	Return/Silt	GND	VA05053955
DG05-284C	12.19	13.72	1.53	B290356	Return/Silt	MSED	VA05053955
DG05-284C	13.72	15.24	1.52	B290357	Return/Silt	MSED	VA05053955
DG05-284C	15.24	16.76	1.52	B290358	Return/Silt	MSED	VA05053955
DG05-284C	16.76	18.29	1.53	B290359	Return/Silt	MSED	VA05053955
DG05-284C	18.29	19.81	1.52	B290360	Return/Silt	GND	VA05053955
DG05-284C	19.81	21.34	1.53	B290361	Return/Silt	MSED	VA05053955
DG05-284C	22.86	24.38	1.52	B290362	Return/Silt	MSED	VA05053955
DG05-284C	24.38	25.91	1.53	B290363	Return/Silt	MSED	VA05053955
DG05-284C	25.91	27.43	1.52	B290364	Return/Silt	MSED	VA05053955
DG05-284C	27.43	28.96	1.53	B290365	Return/Silt	MSED	VA05053955
DG05-284C	28.96	30.48	1.52	B290366	Return/Silt	MSED	VA05053955
DG05-284C	30.48	32.00	1.52	B290367	Return/Silt	MSED	VA05053955
DG05-284C	32.00	33.53	1.53	B290368	Return/Silt	MSED	VA05053955
DG05-284C	33.53	35.05	1.52	B290369	Return/Silt	MSED	VA05053955
DG05-284C	35.05	36.58	1.53	B290370	Return/Silt	MSED	VA05053955
DG05-284C	36.58	38.10	1.52	B290371	Return/Silt	MSED	VA05053955
DG05-284C	38.10	39.62	1.52	B290372	Return/Silt	MSED	VA05053955
DG05-284C	39.62	41.15	1.53	B290373	Return/Silt	MSED	VA05053955
DG05-284C	41.15	42.67	1.52	B290374	Return/Silt	MSED	VA05053955
DG05-284C	42.67	44.20	1.53	B290375	Return/Silt	MSED	VA05053955
DG05-284C	44.20	45.72	1.52	B290376	Return/Silt	MSED	VA05053955
DG05-284C	45.72	47.24	1.52	B290377	Return/Silt	MSED	VA05053955
DG05-284C	47.24	48.77	1.53	B290378	Return/Silt	MSED	VA05053955
DG05-284C	48.77	50.29	1.52	B290379	Return/Silt	MSED	VA05053955
DG05-284C	50.29	51.82	1.53	B290380	Return/Silt	MSED	VA05053955
DG05-284C	51.82	53.34	1.52	B290381	Return/Silt	MSED	VA05053955
DG05-284C	54.86	56.39	1.53	B290382	Return/Silt	MSED	VA05053955
DG05-284C	56.39	57.91	1.52	B290383	Return/Silt	MSED	VA05053955
DG05-284C	57.91	59.44	1.53	B290384	Return/Silt	MSED	VA05053955
DG05-284C	59.44	60.96	1.52	B290385	Return/Silt	MSED	VA05053955
DG05-284C	60.96	62.48	1.52	B290386	Return/Silt	MSED	VA05053955

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-276C	15.24	16.76	1.52	290101	Return/Silt	GND	VA05045076
DG05-276C	16.76	18.29	1.53	290102	Return/Silt	GND	VA05045076
DG05-276C	18.29	19.81	1.52	290103	Return/Silt	GND	VA05045076
DG05-276C	19.81	21.34	1.53	209104	Return/Silt	GND	VA05045076
DG05-276C	21.34	22.86	1.52	209105	Return/Silt	GND	VA05045076
DG05-276C	22.86	24.38	1.52	290106	Return/Silt	GND	VA05045076
DG05-276C	24.38	25.91	1.53	290107	Return/Silt	GND	VA05045076
DG05-276C	25.91	27.43	1.52	290108	Return/Silt	GND	VA05045076
DG05-276C	38.1	39.62	1.52	290109	Return/Silt	GND	VA05045076
DG05-276C	39.62	41.16	1.54	290110	Return/Silt	GND	VA05045076
DG05-277C	18.21	19.81	1.6	290111	Return/Silt	GND	VA05045076
DG05-277C	19.81	21.34	1.53	290112	Return/Silt	GND	VA05045076
DG05-277C	21.34	22.86	1.52	290113	Return/Silt	GND	VA05045076
DG05-278C	No Return after casing						
DG05-279C							
DG05-280C	22.86	24.38	1.52	290114	Return/Silt	GND	VA05047184
DG05-280C	24.38	25.91	1.53	290115	Return/Silt	GND	VA05047184
DG05-280C	25.91	27.43	1.52	290116	Return/Silt	GND	VA05047184
DG05-280C	27.43	28.96	1.53	290117	Return/Silt	GND	VA05047184
DG05-280C	28.96	30.48	1.52	290118	Return/Silt	GND	VA05047184
DG05-280C	30.48	32.00	1.52	290119	Return/Silt	GND	VA05047184
DG05-280C	32.00	33.53	1.53	290120	Return/Silt	GND	VA05047184
DG05-280C	33.53	35.05	1.52	290121	Return/Silt	GND	VA05047184
DG05-280C	35.05	36.58	1.53	290122	Return/Silt	GND	VA05047184
DG05-280C	36.58	38.10	1.52	290123	Return/Silt	GND	VA05047184
DG05-280C	38.10	39.62	1.52	290124	Return/Silt	GND	VA05047184
DG05-280C	39.62	41.15	1.53	290125	Return/Silt	GND	VA05047184
DG05-280C	41.15	42.67	1.52	290126	Return/Silt	GND	VA05047184
DG05-280C	42.67	44.20	1.53	290127	Return/Silt	GND	VA05047184
DG05-280C	44.20	45.72	1.52	290128	Return/Silt	GND	VA05047184
DG05-280C	45.72	47.24	1.52	290129	Return/Silt	GND	VA05047184
DG05-280C	47.24	48.77	1.53	290130	Return/Silt	GND	VA05047184
DG05-280C	48.77	50.29	1.52	290131	Return/Silt	GND	VA05047184
DG05-280C	50.29	51.82	1.53	290132	Return/Silt	GND	VA05047184
DG05-280C	51.82	53.34	1.52	290133	Return/Silt	GND	VA05047184
DG05-280C	53.34	54.86	1.52	290134	Return/Silt	GND	VA05047184
DG05-280C	54.86	56.39	1.53	290135	Return/Silt	GND	VA05047184
DG05-280C	56.39	57.91	1.52	290136	Return/Silt	GND	VA05047184
DG05-280C	57.91	59.44	1.53	290137	Return/Silt	GND	VA05047184
DG05-280C	59.44	60.96	1.52	290138	Return/Silt	GND	VA05047184
DG05-280C	60.96	62.48	1.52	290139	Return/Silt	GND	VA05047184
DG05-280C	62.48	64.01	1.53	290140	Return/Silt	GND	VA05047184
DG05-280C	64.01	65.53	1.52	290141	Return/Silt	GND	VA05047184
DG05-280C	65.53	67.06	1.53	290142	Return/Silt	GND	VA05047184
DG05-280C	67.06	68.58	1.52	290143	Return/Silt	GND	VA05047184
DG05-280C	68.58	70.10	1.52	290144	Return/Silt	GND	VA05047184
DG05-280C	70.10	71.63	1.53	290145	Return/Silt	GND	VA05047184
DG05-280C	71.63	73.15	1.52	290146	Return/Silt	GND	VA05047184
DG05-280C	73.15	74.68	1.53	290147	Return/Silt	GND	VA05047184
DG05-280C	74.68	76.20	1.52	290148	Return/Silt	GND	VA05047184
DG05-280C	76.20	77.72	1.52	290149	Return/Silt	GND	VA05047184
DG05-280C	77.72	79.25	1.53	290150	Return/Silt	GND	VA05047184
DG05-280C	79.25	80.77	1.52	290151	Return/Silt	GND	VA05047184
DG05-280C	80.77	82.30	1.53	290152	Return/Silt	GND	VA05047184
DG05-280C	94.49	96.01	1.52	290153	Return/Silt	GND	VA05047184
DG05-280C	96.01	97.54	1.53	290154	Return/Silt	GND	VA05047184
DG05-280C	97.54	99.06	1.52	290155	Return/Silt	GND	VA05047184
DG05-280C	99.06	100.58	1.52	290156	Return/Silt	GND	VA05047184
DG05-280C	100.58	102.11	1.53	290157	Return/Silt	GND	VA05047184

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-280C	102.11	103.63	1.52	290158	Return/Silt	GND	VA05047184
DG05-280C	103.63	105.16	1.53	290159	Return/Silt	GND	VA05047826
DG05-280C	105.16	106.68	1.52	290160	Return/Silt	GND	VA05047826
DG05-280C	106.68	108.20	1.52	290161	Return/Silt	GND	VA05047826
DG05-280C	108.20	109.73	1.53	290162	Return/Silt	GND	VA05047826
DG05-280C	109.73	111.25	1.52	290163	Return/Silt	GND	VA05047826
DG05-280C	111.25	112.78	1.53	290164	Return/Silt	GND	VA05047826
DG05-280C	112.78	114.30	1.52	290165	Return/Silt	GND	VA05047826
DG05-280C	114.30	115.87	1.57	290166	Return/Silt	GND	VA05047826
DG05-280C	115.87	117.35	1.48	290167	Return/Silt	GND	VA05047826
DG05-280C	117.35	118.87	1.52	290168	Return/Silt	GND	VA05047826
DG05-280C	118.87	120.40	1.53	290169	Return/Silt	GND	VA05047826
DG05-280C	120.40	121.92	1.52	290170	Return/Silt	GND	VA05047826
DG05-280C	121.92	123.44	1.52	290171	Return/Silt	GND	VA05047826
DG05-280C	123.44	124.97	1.53	290172	Return/Silt	GND	VA05047826
DG05-280C	124.97	126.49	1.52	290173	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290174	Return/Silt	GND	VA05047826
DG05-280C	129.54	131.06	1.52	290175	Return/Silt	GND	VA05047826
DG05-280C	131.06	132.59	1.53	290176	Return/Silt	GND	VA05047826
DG05-280C	132.59	134.11	1.52	290177	Return/Silt	GND	VA05047826
DG05-280C	134.11	135.64	1.53	290178	Return/Silt	GND	VA05047826
DG05-280C	135.64	137.16	1.52	290179	Return/Silt	GND	VA05047826
DG05-280C	137.16	138.68	1.52	290180	Return/Silt	GND	VA05047826
DG05-280C	138.68	140.21	1.53	290181	Return/Silt	GND	VA05047826
DG05-280C	140.21	141.73	1.52	290182	Return/Silt	GND	VA05047826
DG05-280C	141.73	143.26	1.53	290183	Return/Silt	GND	VA05047826
DG05-280C	143.26	144.78	1.52	290184	Return/Silt	GND	VA05047826
DG05-280C	144.78	146.30	1.52	290185	Return/Silt	GND	VA05047826
DG05-280C	146.30	147.83	1.53	290186	Return/Silt	GND	VA05047826
DG05-280C	147.83	149.35	1.52	290187	Return/Silt	GND	VA05047826
DG05-280C	149.35	150.88	1.53	290188	Return/Silt	GND	VA05047826
DG05-280C	150.88	152.40	1.52	290189	Return/Silt	GND	VA05047826
DG05-280C	192.02	193.55	1.53	290190	Return/Silt	GND	VA05047826
DG05-280C	193.55	195.07	1.52	290191	Return/Silt	GND	VA05047826
DG05-280C	195.07	196.60	1.53	290192	Return/Silt	GND	VA05047826
DG05-280C	196.60	198.12	1.52	290193	Return/Silt	GND	VA05047826
DG05-280C	198.12	199.64	1.52	290194	Return/Silt	GND	VA05047826
DG05-280C	199.64	201.17	1.53	290195	Return/Silt	GND	VA05047826
DG05-280C	201.17	202.69	1.52	290196	Return/Silt	GND	VA05047826
DG05-280C	202.69	204.22	1.53	290197	Return/Silt	GND	VA05047826
DG05-280C	204.22	205.74	1.52	290198	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290199	Return/Silt	GND	VA05048596
DG05-281C	25.91	27.43	1.52	290200	Return/Silt	GND	VA05048596
DG05-281C	27.43	28.96	1.53	290201	Return/Silt	GND	VA05048596
DG05-281C	28.96	30.48	1.52	290202	Return/Silt	GND	VA05048596
DG05-281C	30.48	32.00	1.52	290203	Return/Silt	GND	VA05048596
DG05-281C	32.00	33.53	1.53	290204	Return/Silt	GND	VA05048596
DG05-281C	33.53	35.06	1.53	290205	Return/Silt	GND	VA05048596
DG05-281C	35.06	36.58	1.52	290206	Return/Silt	GND	VA05048596
DG05-281C	36.58	38.10	1.52	290207	Return/Silt	GND	VA05048596
DG05-281C	38.10	39.62	1.52	290208	Return/Silt	GND	VA05048596
DG05-281C	39.62	41.15	1.53	290209	Return/Silt	GND	VA05048596
DG05-281C	41.15	42.67	1.52	290210	Return/Silt	GND	VA05048596
DG05-281C	42.67	44.20	1.53	290211	Return/Silt	GND	VA05048596
DG05-281C	44.20	45.72	1.52	290212	Return/Silt	GND	VA05048596
DG05-281C	45.72	47.24	1.52	290213	Return/Silt	GND	VA05048596
DG05-281C	47.24	48.77	1.53	290214	Return/Silt	GND	VA05048596
DG05-281C	48.77	50.29	1.52	290215	Return/Silt	GND	VA05048596
DG05-281C	50.29	51.82	1.53	290216	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-281C	51.82	53.34	1.52	290217	Return/Silt	GND	VA05048596
DG05-281C	53.34	54.86	1.52	290218	Return/Silt	GND	VA05048596
DG05-281C	54.86	56.39	1.53	290219	Return/Silt	GND	VA05048596
DG05-281C	56.39	57.91	1.52	290220	Return/Silt	GND	VA05048596
DG05-281C	57.91	59.44	1.53	290221	Return/Silt	GND	VA05048596
DG05-281C	59.44	60.96	1.52	290222	Return/Silt	GND	VA05048596
DG05-281C	60.96	62.48	1.52	290223	Return/Silt	GND	VA05048596
DG05-281C	62.48	64.01	1.53	290224	Return/Silt	GND	VA05048596
DG05-281C	64.01	65.53	1.52	290225	Return/Silt	GND	VA05048596
DG05-281C	65.53	67.06	1.53	290226	Return/Silt	GND	VA05048596
DG05-281C	67.06	68.58	1.52	290227	Return/Silt	GND	VA05048596
DG05-281C	68.58	70.10	1.52	290228	Return/Silt	GND	VA05048596
DG05-281C	70.10	71.63	1.53	290229	Return/Silt	GND	VA05048596
DG05-281C	71.63	74.68	3.05	290230	Return/Silt	GND	VA05048596
DG05-281C	74.68	76.20	1.52	290231	Return/Silt	GND	VA05048596
DG05-281C	76.20	77.72	1.52	290232	Return/Silt	GND	VA05048596
DG05-281C	77.72	79.25	1.53	290233	Return/Silt	GND	VA05048596
DG05-281C	79.25	80.77	1.52	290234	Return/Silt	GND	VA05048596
DG05-281C	80.77	82.30	1.53	290235	Return/Silt	GND	VA05048596
DG05-281C	82.30	83.82	1.52	290236	Return/Silt	GND	VA05048596
DG05-281C	83.82	85.39	1.57	290237	Return/Silt	GND	VA05048596
DG05-281C	85.39	86.87	1.48	290238	Return/Silt	GND	VA05048596
DG05-281C	86.87	88.39	1.52	290239	Return/Silt	GND	VA05048596
DG05-281C	88.39	89.92	1.53	290240	Return/Silt	GND	VA05048596
DG05-281C	89.92	91.44	1.52	290241	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290242	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290243	Return/Silt	GND	VA05048596
DG05-281C	92.96	94.49	1.53	290244	Return/Silt	GND	VA05048596
DG05-281C	94.49	96.01	1.52	290245	Return/Silt	GND	VA05048596
DG05-281C	96.01	97.54	1.53	290246	Return/Silt	GND	VA05048596
DG05-281C	97.54	99.06	1.52	290247	Return/Silt	GND	VA05048596
DG05-281C	99.06	100.58	1.52	290248	Return/Silt	GND	VA05048596
DG05-281C	100.58	102.11	1.53	290249	Return/Silt	GND	VA05048596
DG05-281C	102.11	103.63	1.52	290250	Return/Silt	GND	VA05048596
DG05-281C	103.63	105.16	1.53	290251	Return/Silt	GND	VA05048596
DG05-281C	105.16	106.68	1.52	290252	Return/Silt	GND	VA05048596
DG05-281C	106.68	108.20	1.52	290253	Return/Silt	GND	VA05048596
DG05-281C	108.20	109.73	1.53	290254	Return/Silt	GND	VA05048596
DG05-281C	109.73	111.25	1.52	290255	Return/Silt	GND	VA05048596
DG05-281C	111.25	112.78	1.53	290256	Return/Silt	GND	VA05048596
DG05-281C	112.78	114.30	1.52	290257	Return/Silt	GND	VA05048596
DG05-281C	114.30	115.82	1.52	290258	Return/Silt	GND	VA05048596
DG05-281C	115.82	117.35	1.53	290259	Return/Silt	GND	VA05048596
DG05-281C	117.35	118.87	1.52	290260	Return/Silt	GND	VA05048596
DG05-281C	118.87	120.40	1.53	290261	Return/Silt	GND	VA05048596
DG05-281C	120.40	121.92	1.52	290262	Return/Silt	GND	VA05048596
DG05-281C	121.92	123.44	1.52	290263	Return/Silt	GND	VA05048596
DG05-281C	123.44	124.97	1.53	290264	Return/Silt	GND	VA05048596
DG05-281C	124.97	126.49	1.52	290265	Return/Silt	GND	VA05048596
DG05-282C	15.24	16.76	1.52	290266	Return/Silt	GND	VA05048596
DG05-282C	30.48	32.00	1.52	290267	Return/Silt	GND	VA05048596
DG05-282C	32.00	33.53	1.53	290268	Return/Silt	GND	VA05048596
DG05-282C	33.53	35.05	1.52	290269	Return/Silt	GND	VA05048596
DG05-282C	35.05	36.58	1.53	290270	Return/Silt	GND	VA05048596
DG05-282C	36.58	38.10	1.52	290271	Return/Silt	GND	VA05048596
DG05-282C	38.10	39.66	1.56	290272	Return/Silt	GND	VA05048596
DG05-282C	39.66	41.15	1.49	290273	Return/Silt	GND	VA05048596
DG05-282C	41.15	42.67	1.52	290274	Return/Silt	GND	VA05048596
DG05-282C	42.67	44.20	1.53	290275	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	86.87	88.39	1.52	290276	Return/Silt	GND	VA05048596
DG05-282C	88.39	89.92	1.53	290277	Return/Silt	GND	VA05048596
DG05-282C	89.92	91.44	1.52	290278	Return/Silt	GND	VA05048596
DG05-282C	91.44	92.96	1.52	290279	Return/Silt	GND	VA05048596
DG05-282C	92.96	94.49	1.53	290280	Return/Silt	GND	VA05048596
DG05-282C	94.49	96.01	1.52	290281	Return/Silt	GND	VA05048596
DG05-282C	96.01	97.54	1.53	290282	Return/Silt	GND	VA05048596
DG05-282C	97.54	99.06	1.52	290283	Return/Silt	GND	VA05048596
DG05-282C	99.06	100.58	1.52	290284	Return/Silt	GND	VA05048596
DG05-282C	100.58	102.11	1.53	290285	Return/Silt	GND	VA05048596
DG05-282C	102.11	103.63	1.52	290286	Return/Silt	GND	VA05048596
DG05-282C	103.63	105.16	1.53	290287	Return/Silt	GND	VA05048596
DG05-282C	105.16	106.68	1.52	290288	Return/Silt	GND	VA05048596
DG05-282C	106.68	108.20	1.52	290289	Return/Silt	GND	VA05048596
DG05-282C	108.20	109.73	1.53	290290	Return/Silt	GND	VA05048596
DG05-282C	114.30	115.82	1.52	290291	Return/Silt	GND	VA05048596
DG05-282C	115.82	117.35	1.53	290292	Return/Silt	GND	VA05048596
DG05-282C	117.35	118.87	1.52	290293	Return/Silt	GND	VA05048596
DG05-282C	118.87	120.40	1.53	290294	Return/Silt	GND	VA05048596
DG05-282C	120.40	121.92	1.52	290295	Return/Silt	GND	VA05048596
DG05-282C	121.92	123.44	1.52	290296	Return/Silt	GND	VA05048596
DG05-282C	123.44	124.97	1.53	290297	Return/Silt	GND	VA05048596
DG05-282C	124.97	126.49	1.52	290298	Return/Silt	GND	VA05048596
DG05-282C	126.49	128.02	1.53	290299	Return/Silt	GND	VA05048596
DG05-282C	128.02	129.54	1.52	290300	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290301	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290302	Return/Silt	GND	VA05048596
DG05-282C	131.06	132.59	1.53	290303	Return/Silt	GND	VA05048596
DG05-282C	132.59	134.11	1.52	290304	Return/Silt	GND	VA05048596
DG05-282C	134.11	135.64	1.53	290305	Return/Silt	GND	VA05048596
DG05-282C	135.64	137.16	1.52	290306	Return/Silt	GND	VA05048596
DG05-282C	137.16	138.68	1.52	290307	Return/Silt	GND	VA05048596
DG05-282C	138.68	140.21	1.53	290308	Return/Silt	GND	VA05048596
DG05-282C	140.21	141.73	1.52	290309	Return/Silt	GND	VA05048596
DG05-282C	141.73	143.26	1.53	290310	Return/Silt	GND	VA05048596
DG05-282C	144.78	146.30	1.52	290311	Return/Silt	GND	VA05048596
DG05-282C	146.30	147.83	1.53	290312	Return/Silt	GND	VA05048596
DG05-282C	147.83	149.35	1.52	290313	Return/Silt	GND	VA05048596
DG05-282C	149.35	150.88	1.53	290314	Return/Silt	GND	VA05048596
DG05-282C	150.88	152.40	1.52	290315	Return/Silt	GND	VA05048596
DG05-282C	152.40	153.92	1.52	290316	Return/Silt	GND	VA05048596
DG05-282C	153.92	155.45	1.53	290317	Return/Silt	GND	VA05048596
DG05-282C	155.45	156.97	1.52	290318	Return/Silt	GND	VA05048596
DG05-282C	156.97	158.50	1.53	290319	Return/Silt	GND	VA05048596
DG05-282C	158.50	160.02	1.52	290320	Return/Silt	GND	VA05048596
DG05-282C	160.02	161.54	1.52	290321	Return/Silt	GND	VA05048596
DG05-282C	161.54	163.07	1.53	290322	Return/Silt	GND	VA05048596
DG05-282C	163.07	164.59	1.52	290323	Return/Silt	GND	VA05048596
DG05-282C	164.59	166.12	1.53	290324	Return/Silt	GND	VA05048596
DG05-282C	166.12	167.64	1.52	290325	Return/Silt	GND	VA05048596
DG05-282C	111.25	112.78	1.53	290326	Return/Silt	GND	VA05049478
DG05-280C	22.86	24.38	1.52	290327	Return/Silt	GND	VA05049478
DG05-282C	109.73	111.25	1.52	290328	Return/Silt	GND	VA05049478
DG05-282C	112.78	114.30	1.52	290329	Return/Silt	GND	VA05049478
DG05-282C	196.60	198.12	1.52	290330	Return/Silt	MSED	VA05049478
DG05-282C	198.12	199.64	1.52	290331	Return/Silt	MSED	VA05049478
DG05-282C	199.64	201.17	1.52	290332	Return/Silt	MSED	VA05049478
DG05-282C	201.17	202.69	1.53	290333	Return/Silt	MSED	VA05049478
DG05-282C	202.69	204.22	1.52	290334	Return/Silt	MSED	VA05049478

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	204.22	205.74	1.53	290335	Return/Silt	MSED	VA05049478
DG05-282C	205.74	207.26	1.52	290336	Return/Silt	MSED	VA05049478
DG05-282C	242.32	243.84	1.52	290337	Return/Silt	MSED	VA05049478
DG05-282C	245.36	246.89	1.52	290338	Return/Silt	MSED	VA05049478
DG05-282C	246.89	248.41	1.53	290339	Return/Silt	MSED	VA05049478
DG05-282C	248.41	249.94	1.52	290340	Return/Silt	MSED	VA05049478
DG05-282C	249.94	251.46	1.53	290341	Return/Silt	MSED	VA05049478
DG05-282C	251.46	252.98	1.52	290342	Return/Silt	MSED	VA05049478
DG05-283C	24.38	25.91	1.53	B290343	Return/Silt	GND	VA05053955
DG05-283C	25.91	27.43	1.52	B290344	Return/Silt	GND	VA05053955
DG05-283C	27.43	28.96	1.53	B290345	Return/Silt	GND	VA05053955
DG05-283C	28.96	30.48	1.52	B290346	Return/Silt	GND	VA05053955
DG05-283C	30.48	32.00	1.52	B290347	Return/Silt	GND	VA05053955
DG05-283C	32.00	33.53	1.53	B290348	Return/Silt	GND	VA05053955
DG05-283C	33.53	35.05	1.52	B290349	Return/Silt	GND	VA05053955
DG05-283C	35.05	36.58	1.53	B290350	Return/Silt	GND	VA05053955
DG05-283C	36.58	38.10	1.52	B290351	Return/Silt	GND	VA05053955
DG05-283C	38.10	39.62	1.52	B290352	Return/Silt	GND	VA05053955
DG05-283C	39.62	41.15	1.53	B290353	Return/Silt	GND	VA05053955
DG05-283C	41.15	42.67	1.52	B290354	Return/Silt	GND	VA05053955
DG05-283C	42.67	44.20	1.53	B290355	Return/Silt	GND	VA05053955
DG05-284C	12.19	13.72	1.53	B290356	Return/Silt	MSED	VA05053955
DG05-284C	13.72	15.24	1.52	B290357	Return/Silt	MSED	VA05053955
DG05-284C	15.24	16.76	1.52	B290358	Return/Silt	MSED	VA05053955
DG05-284C	16.76	18.29	1.53	B290359	Return/Silt	MSED	VA05053955
DG05-284C	18.29	19.81	1.52	B290360	Return/Silt	GND	VA05053955
DG05-284C	19.81	21.34	1.53	B290361	Return/Silt	MSED	VA05053955
DG05-284C	22.86	24.38	1.52	B290362	Return/Silt	MSED	VA05053955
DG05-284C	24.38	25.91	1.53	B290363	Return/Silt	MSED	VA05053955
DG05-284C	25.91	27.43	1.52	B290364	Return/Silt	MSED	VA05053955
DG05-284C	27.43	28.96	1.53	B290365	Return/Silt	MSED	VA05053955
DG05-284C	28.96	30.48	1.52	B290366	Return/Silt	MSED	VA05053955
DG05-284C	30.48	32.00	1.52	B290367	Return/Silt	MSED	VA05053955
DG05-284C	32.00	33.53	1.53	B290368	Return/Silt	MSED	VA05053955
DG05-284C	33.53	35.05	1.52	B290369	Return/Silt	MSED	VA05053955
DG05-284C	35.05	36.58	1.53	B290370	Return/Silt	MSED	VA05053955
DG05-284C	36.58	38.10	1.52	B290371	Return/Silt	MSED	VA05053955
DG05-284C	38.10	39.62	1.52	B290372	Return/Silt	MSED	VA05053955
DG05-284C	39.62	41.15	1.53	B290373	Return/Silt	MSED	VA05053955
DG05-284C	41.15	42.67	1.52	B290374	Return/Silt	MSED	VA05053955
DG05-284C	42.67	44.20	1.53	B290375	Return/Silt	MSED	VA05053955
DG05-284C	44.20	45.72	1.52	B290376	Return/Silt	MSED	VA05053955
DG05-284C	45.72	47.24	1.52	B290377	Return/Silt	MSED	VA05053955
DG05-284C	47.24	48.77	1.53	B290378	Return/Silt	MSED	VA05053955
DG05-284C	48.77	50.29	1.52	B290379	Return/Silt	MSED	VA05053955
DG05-284C	50.29	51.82	1.53	B290380	Return/Silt	MSED	VA05053955
DG05-284C	51.82	53.34	1.52	B290381	Return/Silt	MSED	VA05053955
DG05-284C	54.86	56.39	1.53	B290382	Return/Silt	MSED	VA05053955
DG05-284C	56.39	57.91	1.52	B290383	Return/Silt	MSED	VA05053955
DG05-284C	57.91	59.44	1.53	B290384	Return/Silt	MSED	VA05053955
DG05-284C	59.44	60.96	1.52	B290385	Return/Silt	MSED	VA05053955
DG05-284C	60.96	62.48	1.52	B290386	Return/Silt	MSED	VA05053955

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-276C	15.24	16.76	1.52	290101	Return/Silt	GND	VA05045076
DG05-276C	16.76	18.29	1.53	290102	Return/Silt	GND	VA05045076
DG05-276C	18.29	19.81	1.52	290103	Return/Silt	GND	VA05045076
DG05-276C	19.81	21.34	1.53	209104	Return/Silt	GND	VA05045076
DG05-276C	21.34	22.86	1.52	209105	Return/Silt	GND	VA05045076
DG05-276C	22.86	24.38	1.52	290106	Return/Silt	GND	VA05045076
DG05-276C	24.38	25.91	1.53	290107	Return/Silt	GND	VA05045076
DG05-276C	25.91	27.43	1.52	290108	Return/Silt	GND	VA05045076
DG05-276C	38.1	39.62	1.52	290109	Return/Silt	GND	VA05045076
DG05-276C	39.62	41.16	1.54	290110	Return/Silt	GND	VA05045076
DG05-277C	18.21	19.81	1.6	290111	Return/Silt	GND	VA05045076
DG05-277C	19.81	21.34	1.53	290112	Return/Silt	GND	VA05045076
DG05-277C	21.34	22.86	1.52	290113	Return/Silt	GND	VA05045076
DG05-278C	No Return after casing						
DG05-279C							
DG05-280C	22.86	24.38	1.52	290114	Return/Silt	GND	VA05047184
DG05-280C	24.38	25.91	1.53	290115	Return/Silt	GND	VA05047184
DG05-280C	25.91	27.43	1.52	290116	Return/Silt	GND	VA05047184
DG05-280C	27.43	28.96	1.53	290117	Return/Silt	GND	VA05047184
DG05-280C	28.96	30.48	1.52	290118	Return/Silt	GND	VA05047184
DG05-280C	30.48	32.00	1.52	290119	Return/Silt	GND	VA05047184
DG05-280C	32.00	33.53	1.53	290120	Return/Silt	GND	VA05047184
DG05-280C	33.53	35.05	1.52	290121	Return/Silt	GND	VA05047184
DG05-280C	35.05	36.58	1.53	290122	Return/Silt	GND	VA05047184
DG05-280C	36.58	38.10	1.52	290123	Return/Silt	GND	VA05047184
DG05-280C	38.10	39.62	1.52	290124	Return/Silt	GND	VA05047184
DG05-280C	39.62	41.15	1.53	290125	Return/Silt	GND	VA05047184
DG05-280C	41.15	42.67	1.52	290126	Return/Silt	GND	VA05047184
DG05-280C	42.67	44.20	1.53	290127	Return/Silt	GND	VA05047184
DG05-280C	44.20	45.72	1.52	290128	Return/Silt	GND	VA05047184
DG05-280C	45.72	47.24	1.52	290129	Return/Silt	GND	VA05047184
DG05-280C	47.24	48.77	1.53	290130	Return/Silt	GND	VA05047184
DG05-280C	48.77	50.29	1.52	290131	Return/Silt	GND	VA05047184
DG05-280C	50.29	51.82	1.53	290132	Return/Silt	GND	VA05047184
DG05-280C	51.82	53.34	1.52	290133	Return/Silt	GND	VA05047184
DG05-280C	53.34	54.86	1.52	290134	Return/Silt	GND	VA05047184
DG05-280C	54.86	56.39	1.53	290135	Return/Silt	GND	VA05047184
DG05-280C	56.39	57.91	1.52	290136	Return/Silt	GND	VA05047184
DG05-280C	57.91	59.44	1.53	290137	Return/Silt	GND	VA05047184
DG05-280C	59.44	60.96	1.52	290138	Return/Silt	GND	VA05047184
DG05-280C	60.96	62.48	1.52	290139	Return/Silt	GND	VA05047184
DG05-280C	62.48	64.01	1.53	290140	Return/Silt	GND	VA05047184
DG05-280C	64.01	65.53	1.52	290141	Return/Silt	GND	VA05047184
DG05-280C	65.53	67.06	1.53	290142	Return/Silt	GND	VA05047184
DG05-280C	67.06	68.58	1.52	290143	Return/Silt	GND	VA05047184
DG05-280C	68.58	70.10	1.52	290144	Return/Silt	GND	VA05047184
DG05-280C	70.10	71.63	1.53	290145	Return/Silt	GND	VA05047184
DG05-280C	71.63	73.15	1.52	290146	Return/Silt	GND	VA05047184
DG05-280C	73.15	74.68	1.53	290147	Return/Silt	GND	VA05047184
DG05-280C	74.68	76.20	1.52	290148	Return/Silt	GND	VA05047184
DG05-280C	76.20	77.72	1.52	290149	Return/Silt	GND	VA05047184
DG05-280C	77.72	79.25	1.53	290150	Return/Silt	GND	VA05047184
DG05-280C	79.25	80.77	1.52	290151	Return/Silt	GND	VA05047184
DG05-280C	80.77	82.30	1.53	290152	Return/Silt	GND	VA05047184
DG05-280C	94.49	96.01	1.52	290153	Return/Silt	GND	VA05047184
DG05-280C	96.01	97.54	1.53	290154	Return/Silt	GND	VA05047184
DG05-280C	97.54	99.06	1.52	290155	Return/Silt	GND	VA05047184
DG05-280C	99.06	100.58	1.52	290156	Return/Silt	GND	VA05047184
DG05-280C	100.58	102.11	1.53	290157	Return/Silt	GND	VA05047184

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-280C	102.11	103.63	1.52	290158	Return/Silt	GND	VA05047184
DG05-280C	103.63	105.16	1.53	290159	Return/Silt	GND	VA05047826
DG05-280C	105.16	106.68	1.52	290160	Return/Silt	GND	VA05047826
DG05-280C	106.68	108.20	1.52	290161	Return/Silt	GND	VA05047826
DG05-280C	108.20	109.73	1.53	290162	Return/Silt	GND	VA05047826
DG05-280C	109.73	111.25	1.52	290163	Return/Silt	GND	VA05047826
DG05-280C	111.25	112.78	1.53	290164	Return/Silt	GND	VA05047826
DG05-280C	112.78	114.30	1.52	290165	Return/Silt	GND	VA05047826
DG05-280C	114.30	115.87	1.57	290166	Return/Silt	GND	VA05047826
DG05-280C	115.87	117.35	1.48	290167	Return/Silt	GND	VA05047826
DG05-280C	117.35	118.87	1.52	290168	Return/Silt	GND	VA05047826
DG05-280C	118.87	120.40	1.53	290169	Return/Silt	GND	VA05047826
DG05-280C	120.40	121.92	1.52	290170	Return/Silt	GND	VA05047826
DG05-280C	121.92	123.44	1.52	290171	Return/Silt	GND	VA05047826
DG05-280C	123.44	124.97	1.53	290172	Return/Silt	GND	VA05047826
DG05-280C	124.97	126.49	1.52	290173	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290174	Return/Silt	GND	VA05047826
DG05-280C	129.54	131.06	1.52	290175	Return/Silt	GND	VA05047826
DG05-280C	131.06	132.59	1.53	290176	Return/Silt	GND	VA05047826
DG05-280C	132.59	134.11	1.52	290177	Return/Silt	GND	VA05047826
DG05-280C	134.11	135.64	1.53	290178	Return/Silt	GND	VA05047826
DG05-280C	135.64	137.16	1.52	290179	Return/Silt	GND	VA05047826
DG05-280C	137.16	138.68	1.52	290180	Return/Silt	GND	VA05047826
DG05-280C	138.68	140.21	1.53	290181	Return/Silt	GND	VA05047826
DG05-280C	140.21	141.73	1.52	290182	Return/Silt	GND	VA05047826
DG05-280C	141.73	143.26	1.53	290183	Return/Silt	GND	VA05047826
DG05-280C	143.26	144.78	1.52	290184	Return/Silt	GND	VA05047826
DG05-280C	144.78	146.30	1.52	290185	Return/Silt	GND	VA05047826
DG05-280C	146.30	147.83	1.53	290186	Return/Silt	GND	VA05047826
DG05-280C	147.83	149.35	1.52	290187	Return/Silt	GND	VA05047826
DG05-280C	149.35	150.88	1.53	290188	Return/Silt	GND	VA05047826
DG05-280C	150.88	152.40	1.52	290189	Return/Silt	GND	VA05047826
DG05-280C	192.02	193.55	1.53	290190	Return/Silt	GND	VA05047826
DG05-280C	193.55	195.07	1.52	290191	Return/Silt	GND	VA05047826
DG05-280C	195.07	196.60	1.53	290192	Return/Silt	GND	VA05047826
DG05-280C	196.60	198.12	1.52	290193	Return/Silt	GND	VA05047826
DG05-280C	198.12	199.64	1.52	290194	Return/Silt	GND	VA05047826
DG05-280C	199.64	201.17	1.53	290195	Return/Silt	GND	VA05047826
DG05-280C	201.17	202.69	1.52	290196	Return/Silt	GND	VA05047826
DG05-280C	202.69	204.22	1.53	290197	Return/Silt	GND	VA05047826
DG05-280C	204.22	205.74	1.52	290198	Return/Silt	GND	VA05047826
DG05-280C	128.02	129.54	1.52	290199	Return/Silt	GND	VA05048596
DG05-281C	25.91	27.43	1.52	290200	Return/Silt	GND	VA05048596
DG05-281C	27.43	28.96	1.53	290201	Return/Silt	GND	VA05048596
DG05-281C	28.96	30.48	1.52	290202	Return/Silt	GND	VA05048596
DG05-281C	30.48	32.00	1.52	290203	Return/Silt	GND	VA05048596
DG05-281C	32.00	33.53	1.53	290204	Return/Silt	GND	VA05048596
DG05-281C	33.53	35.06	1.53	290205	Return/Silt	GND	VA05048596
DG05-281C	35.06	36.58	1.52	290206	Return/Silt	GND	VA05048596
DG05-281C	36.58	38.10	1.52	290207	Return/Silt	GND	VA05048596
DG05-281C	38.10	39.62	1.52	290208	Return/Silt	GND	VA05048596
DG05-281C	39.62	41.15	1.53	290209	Return/Silt	GND	VA05048596
DG05-281C	41.15	42.67	1.52	290210	Return/Silt	GND	VA05048596
DG05-281C	42.67	44.20	1.53	290211	Return/Silt	GND	VA05048596
DG05-281C	44.20	45.72	1.52	290212	Return/Silt	GND	VA05048596
DG05-281C	45.72	47.24	1.52	290213	Return/Silt	GND	VA05048596
DG05-281C	47.24	48.77	1.53	290214	Return/Silt	GND	VA05048596
DG05-281C	48.77	50.29	1.52	290215	Return/Silt	GND	VA05048596
DG05-281C	50.29	51.82	1.53	290216	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-281C	51.82	53.34	1.52	290217	Return/Silt	GND	VA05048596
DG05-281C	53.34	54.86	1.52	290218	Return/Silt	GND	VA05048596
DG05-281C	54.86	56.39	1.53	290219	Return/Silt	GND	VA05048596
DG05-281C	56.39	57.91	1.52	290220	Return/Silt	GND	VA05048596
DG05-281C	57.91	59.44	1.53	290221	Return/Silt	GND	VA05048596
DG05-281C	59.44	60.96	1.52	290222	Return/Silt	GND	VA05048596
DG05-281C	60.96	62.48	1.52	290223	Return/Silt	GND	VA05048596
DG05-281C	62.48	64.01	1.53	290224	Return/Silt	GND	VA05048596
DG05-281C	64.01	65.53	1.52	290225	Return/Silt	GND	VA05048596
DG05-281C	65.53	67.06	1.53	290226	Return/Silt	GND	VA05048596
DG05-281C	67.06	68.58	1.52	290227	Return/Silt	GND	VA05048596
DG05-281C	68.58	70.10	1.52	290228	Return/Silt	GND	VA05048596
DG05-281C	70.10	71.63	1.53	290229	Return/Silt	GND	VA05048596
DG05-281C	71.63	74.68	3.05	290230	Return/Silt	GND	VA05048596
DG05-281C	74.68	76.20	1.52	290231	Return/Silt	GND	VA05048596
DG05-281C	76.20	77.72	1.52	290232	Return/Silt	GND	VA05048596
DG05-281C	77.72	79.25	1.53	290233	Return/Silt	GND	VA05048596
DG05-281C	79.25	80.77	1.52	290234	Return/Silt	GND	VA05048596
DG05-281C	80.77	82.30	1.53	290235	Return/Silt	GND	VA05048596
DG05-281C	82.30	83.82	1.52	290236	Return/Silt	GND	VA05048596
DG05-281C	83.82	85.39	1.57	290237	Return/Silt	GND	VA05048596
DG05-281C	85.39	86.87	1.48	290238	Return/Silt	GND	VA05048596
DG05-281C	86.87	88.39	1.52	290239	Return/Silt	GND	VA05048596
DG05-281C	88.39	89.92	1.53	290240	Return/Silt	GND	VA05048596
DG05-281C	89.92	91.44	1.52	290241	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290242	Return/Silt	GND	VA05048596
DG05-281C	91.44	92.96	1.52	290243	Return/Silt	GND	VA05048596
DG05-281C	92.96	94.49	1.53	290244	Return/Silt	GND	VA05048596
DG05-281C	94.49	96.01	1.52	290245	Return/Silt	GND	VA05048596
DG05-281C	96.01	97.54	1.53	290246	Return/Silt	GND	VA05048596
DG05-281C	97.54	99.06	1.52	290247	Return/Silt	GND	VA05048596
DG05-281C	99.06	100.58	1.52	290248	Return/Silt	GND	VA05048596
DG05-281C	100.58	102.11	1.53	290249	Return/Silt	GND	VA05048596
DG05-281C	102.11	103.63	1.52	290250	Return/Silt	GND	VA05048596
DG05-281C	103.63	105.16	1.53	290251	Return/Silt	GND	VA05048596
DG05-281C	105.16	106.68	1.52	290252	Return/Silt	GND	VA05048596
DG05-281C	106.68	108.20	1.52	290253	Return/Silt	GND	VA05048596
DG05-281C	108.20	109.73	1.53	290254	Return/Silt	GND	VA05048596
DG05-281C	109.73	111.25	1.52	290255	Return/Silt	GND	VA05048596
DG05-281C	111.25	112.78	1.53	290256	Return/Silt	GND	VA05048596
DG05-281C	112.78	114.30	1.52	290257	Return/Silt	GND	VA05048596
DG05-281C	114.30	115.82	1.52	290258	Return/Silt	GND	VA05048596
DG05-281C	115.82	117.35	1.53	290259	Return/Silt	GND	VA05048596
DG05-281C	117.35	118.87	1.52	290260	Return/Silt	GND	VA05048596
DG05-281C	118.87	120.40	1.53	290261	Return/Silt	GND	VA05048596
DG05-281C	120.40	121.92	1.52	290262	Return/Silt	GND	VA05048596
DG05-281C	121.92	123.44	1.52	290263	Return/Silt	GND	VA05048596
DG05-281C	123.44	124.97	1.53	290264	Return/Silt	GND	VA05048596
DG05-281C	124.97	126.49	1.52	290265	Return/Silt	GND	VA05048596
DG05-282C	15.24	16.76	1.52	290266	Return/Silt	GND	VA05048596
DG05-282C	30.48	32.00	1.52	290267	Return/Silt	GND	VA05048596
DG05-282C	32.00	33.53	1.53	290268	Return/Silt	GND	VA05048596
DG05-282C	33.53	35.05	1.52	290269	Return/Silt	GND	VA05048596
DG05-282C	35.05	36.58	1.53	290270	Return/Silt	GND	VA05048596
DG05-282C	36.58	38.10	1.52	290271	Return/Silt	GND	VA05048596
DG05-282C	38.10	39.66	1.56	290272	Return/Silt	GND	VA05048596
DG05-282C	39.66	41.15	1.49	290273	Return/Silt	GND	VA05048596
DG05-282C	41.15	42.67	1.52	290274	Return/Silt	GND	VA05048596
DG05-282C	42.67	44.20	1.53	290275	Return/Silt	GND	VA05048596

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	86.87	88.39	1.52	290276	Return/Silt	GND	VA05048596
DG05-282C	88.39	89.92	1.53	290277	Return/Silt	GND	VA05048596
DG05-282C	89.92	91.44	1.52	290278	Return/Silt	GND	VA05048596
DG05-282C	91.44	92.96	1.52	290279	Return/Silt	GND	VA05048596
DG05-282C	92.96	94.49	1.53	290280	Return/Silt	GND	VA05048596
DG05-282C	94.49	96.01	1.52	290281	Return/Silt	GND	VA05048596
DG05-282C	96.01	97.54	1.53	290282	Return/Silt	GND	VA05048596
DG05-282C	97.54	99.06	1.52	290283	Return/Silt	GND	VA05048596
DG05-282C	99.06	100.58	1.52	290284	Return/Silt	GND	VA05048596
DG05-282C	100.58	102.11	1.53	290285	Return/Silt	GND	VA05048596
DG05-282C	102.11	103.63	1.52	290286	Return/Silt	GND	VA05048596
DG05-282C	103.63	105.16	1.53	290287	Return/Silt	GND	VA05048596
DG05-282C	105.16	106.68	1.52	290288	Return/Silt	GND	VA05048596
DG05-282C	106.68	108.20	1.52	290289	Return/Silt	GND	VA05048596
DG05-282C	108.20	109.73	1.53	290290	Return/Silt	GND	VA05048596
DG05-282C	114.30	115.82	1.52	290291	Return/Silt	GND	VA05048596
DG05-282C	115.82	117.35	1.53	290292	Return/Silt	GND	VA05048596
DG05-282C	117.35	118.87	1.52	290293	Return/Silt	GND	VA05048596
DG05-282C	118.87	120.40	1.53	290294	Return/Silt	GND	VA05048596
DG05-282C	120.40	121.92	1.52	290295	Return/Silt	GND	VA05048596
DG05-282C	121.92	123.44	1.52	290296	Return/Silt	GND	VA05048596
DG05-282C	123.44	124.97	1.53	290297	Return/Silt	GND	VA05048596
DG05-282C	124.97	126.49	1.52	290298	Return/Silt	GND	VA05048596
DG05-282C	126.49	128.02	1.53	290299	Return/Silt	GND	VA05048596
DG05-282C	128.02	129.54	1.52	290300	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290301	Return/Silt	GND	VA05048596
DG05-282C	129.54	131.06	1.52	290302	Return/Silt	GND	VA05048596
DG05-282C	131.06	132.59	1.53	290303	Return/Silt	GND	VA05048596
DG05-282C	132.59	134.11	1.52	290304	Return/Silt	GND	VA05048596
DG05-282C	134.11	135.64	1.53	290305	Return/Silt	GND	VA05048596
DG05-282C	135.64	137.16	1.52	290306	Return/Silt	GND	VA05048596
DG05-282C	137.16	138.68	1.52	290307	Return/Silt	GND	VA05048596
DG05-282C	138.68	140.21	1.53	290308	Return/Silt	GND	VA05048596
DG05-282C	140.21	141.73	1.52	290309	Return/Silt	GND	VA05048596
DG05-282C	141.73	143.26	1.53	290310	Return/Silt	GND	VA05048596
DG05-282C	144.78	146.30	1.52	290311	Return/Silt	GND	VA05048596
DG05-282C	146.30	147.83	1.53	290312	Return/Silt	GND	VA05048596
DG05-282C	147.83	149.35	1.52	290313	Return/Silt	GND	VA05048596
DG05-282C	149.35	150.88	1.53	290314	Return/Silt	GND	VA05048596
DG05-282C	150.88	152.40	1.52	290315	Return/Silt	GND	VA05048596
DG05-282C	152.40	153.92	1.52	290316	Return/Silt	GND	VA05048596
DG05-282C	153.92	155.45	1.53	290317	Return/Silt	GND	VA05048596
DG05-282C	155.45	156.97	1.52	290318	Return/Silt	GND	VA05048596
DG05-282C	156.97	158.50	1.53	290319	Return/Silt	GND	VA05048596
DG05-282C	158.50	160.02	1.52	290320	Return/Silt	GND	VA05048596
DG05-282C	160.02	161.54	1.52	290321	Return/Silt	GND	VA05048596
DG05-282C	161.54	163.07	1.53	290322	Return/Silt	GND	VA05048596
DG05-282C	163.07	164.59	1.52	290323	Return/Silt	GND	VA05048596
DG05-282C	164.59	166.12	1.53	290324	Return/Silt	GND	VA05048596
DG05-282C	166.12	167.64	1.52	290325	Return/Silt	GND	VA05048596
DG05-282C	111.25	112.78	1.53	290326	Return/Silt	GND	VA05049478
DG05-280C	22.86	24.38	1.52	290327	Return/Silt	GND	VA05049478
DG05-282C	109.73	111.25	1.52	290328	Return/Silt	GND	VA05049478
DG05-282C	112.78	114.30	1.52	290329	Return/Silt	GND	VA05049478
DG05-282C	196.60	198.12	1.52	290330	Return/Silt	MSED	VA05049478
DG05-282C	198.12	199.64	1.52	290331	Return/Silt	MSED	VA05049478
DG05-282C	199.64	201.17	1.52	290332	Return/Silt	MSED	VA05049478
DG05-282C	201.17	202.69	1.53	290333	Return/Silt	MSED	VA05049478
DG05-282C	202.69	204.22	1.52	290334	Return/Silt	MSED	VA05049478

Hole ID	From Depth (m)	To Depth (m)	Sample Interval	Sample #	Sample Type	Host Rock	CSV
DG05-282C	204.22	205.74	1.53	290335	Return/Silt	MSED	VA05049478
DG05-282C	205.74	207.26	1.52	290336	Return/Silt	MSED	VA05049478
DG05-282C	242.32	243.84	1.52	290337	Return/Silt	MSED	VA05049478
DG05-282C	245.36	246.89	1.52	290338	Return/Silt	MSED	VA05049478
DG05-282C	246.89	248.41	1.53	290339	Return/Silt	MSED	VA05049478
DG05-282C	248.41	249.94	1.52	290340	Return/Silt	MSED	VA05049478
DG05-282C	249.94	251.46	1.53	290341	Return/Silt	MSED	VA05049478
DG05-282C	251.46	252.98	1.52	290342	Return/Silt	MSED	VA05049478
DG05-283C	24.38	25.91	1.53	B290343	Return/Silt	GND	VA05053955
DG05-283C	25.91	27.43	1.52	B290344	Return/Silt	GND	VA05053955
DG05-283C	27.43	28.96	1.53	B290345	Return/Silt	GND	VA05053955
DG05-283C	28.96	30.48	1.52	B290346	Return/Silt	GND	VA05053955
DG05-283C	30.48	32.00	1.52	B290347	Return/Silt	GND	VA05053955
DG05-283C	32.00	33.53	1.53	B290348	Return/Silt	GND	VA05053955
DG05-283C	33.53	35.05	1.52	B290349	Return/Silt	GND	VA05053955
DG05-283C	35.05	36.58	1.53	B290350	Return/Silt	GND	VA05053955
DG05-283C	36.58	38.10	1.52	B290351	Return/Silt	GND	VA05053955
DG05-283C	38.10	39.62	1.52	B290352	Return/Silt	GND	VA05053955
DG05-283C	39.62	41.15	1.53	B290353	Return/Silt	GND	VA05053955
DG05-283C	41.15	42.67	1.52	B290354	Return/Silt	GND	VA05053955
DG05-283C	42.67	44.20	1.53	B290355	Return/Silt	GND	VA05053955
DG05-284C	12.19	13.72	1.53	B290356	Return/Silt	MSED	VA05053955
DG05-284C	13.72	15.24	1.52	B290357	Return/Silt	MSED	VA05053955
DG05-284C	15.24	16.76	1.52	B290358	Return/Silt	MSED	VA05053955
DG05-284C	16.76	18.29	1.53	B290359	Return/Silt	MSED	VA05053955
DG05-284C	18.29	19.81	1.52	B290360	Return/Silt	GND	VA05053955
DG05-284C	19.81	21.34	1.53	B290361	Return/Silt	MSED	VA05053955
DG05-284C	22.86	24.38	1.52	B290362	Return/Silt	MSED	VA05053955
DG05-284C	24.38	25.91	1.53	B290363	Return/Silt	MSED	VA05053955
DG05-284C	25.91	27.43	1.52	B290364	Return/Silt	MSED	VA05053955
DG05-284C	27.43	28.96	1.53	B290365	Return/Silt	MSED	VA05053955
DG05-284C	28.96	30.48	1.52	B290366	Return/Silt	MSED	VA05053955
DG05-284C	30.48	32.00	1.52	B290367	Return/Silt	MSED	VA05053955
DG05-284C	32.00	33.53	1.53	B290368	Return/Silt	MSED	VA05053955
DG05-284C	33.53	35.05	1.52	B290369	Return/Silt	MSED	VA05053955
DG05-284C	35.05	36.58	1.53	B290370	Return/Silt	MSED	VA05053955
DG05-284C	36.58	38.10	1.52	B290371	Return/Silt	MSED	VA05053955
DG05-284C	38.10	39.62	1.52	B290372	Return/Silt	MSED	VA05053955
DG05-284C	39.62	41.15	1.53	B290373	Return/Silt	MSED	VA05053955
DG05-284C	41.15	42.67	1.52	B290374	Return/Silt	MSED	VA05053955
DG05-284C	42.67	44.20	1.53	B290375	Return/Silt	MSED	VA05053955
DG05-284C	44.20	45.72	1.52	B290376	Return/Silt	MSED	VA05053955
DG05-284C	45.72	47.24	1.52	B290377	Return/Silt	MSED	VA05053955
DG05-284C	47.24	48.77	1.53	B290378	Return/Silt	MSED	VA05053955
DG05-284C	48.77	50.29	1.52	B290379	Return/Silt	MSED	VA05053955
DG05-284C	50.29	51.82	1.53	B290380	Return/Silt	MSED	VA05053955
DG05-284C	51.82	53.34	1.52	B290381	Return/Silt	MSED	VA05053955
DG05-284C	54.86	56.39	1.53	B290382	Return/Silt	MSED	VA05053955
DG05-284C	56.39	57.91	1.52	B290383	Return/Silt	MSED	VA05053955
DG05-284C	57.91	59.44	1.53	B290384	Return/Silt	MSED	VA05053955
DG05-284C	59.44	60.96	1.52	B290385	Return/Silt	MSED	VA05053955
DG05-284C	60.96	62.48	1.52	B290386	Return/Silt	MSED	VA05053955

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 6-JUN-2005
Account: STRGOL

CERTIFICATE VA05045076

Project: Dublin Gulch-1735

P.O. No.:

This report is for 13 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 9-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045076

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290101		6.56	0.338	1.6	8.79	1580	1420	3.5	24	2.00	<0.5	13	165	318	3.78	3.35
B290102		9.18	1.305	1.5	8.82	1640	1280	3.5	90	2.28	<0.5	16	134	368	4.08	3.36
B290103		4.26	0.329	1.6	8.31	1650	1450	3.5	34	2.22	<0.5	15	144	339	4.53	3.35
B290104		1.94	0.340	<0.5	8.35	1650	1260	3.2	35	2.06	<0.5	14	249	257	4.49	3.30
B290105		3.02	1.060	0.8	8.17	1480	1320	3.1	32	1.80	<0.5	13	179	248	4.19	3.63
B290106		3.92	0.579	0.6	7.62	1375	1290	3.0	19	1.94	<0.5	12	160	190	3.89	3.43
B290107		2.54	0.628	<0.5	7.38	1070	1300	3.0	13	1.90	<0.5	14	182	170	3.94	3.38
B290108		2.08	0.214	1.2	7.44	790	2610	2.9	12	1.78	<0.5	12	260	171	4.22	3.38
B290109		1.58	0.360	<0.5	7.44	605	3500	2.8	3	1.87	<0.5	9	152	108	2.86	3.50
B290110		2.32	0.294	<0.5	7.15	675	3470	2.7	8	1.80	<0.5	9	139	105	2.90	3.35
B290111		1.28	0.411	<0.5	8.58	175	5250	1.8	<2	1.34	<0.5	1	60	69	3.38	0.82
B290112		1.98	0.241	<0.5	8.39	746	1270	2.3	3	1.45	<0.5	7	50	78	2.97	2.06
B290113		2.06	0.626	0.7	8.24	683	2970	1.9	5	1.19	<0.5	3	85	172	3.22	1.54

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045076

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B290101		0.73	349	21	1.53	107	1090	36	0.05	11	383	0.35	48	490	660
B290102		0.73	335	21	1.51	104	1260	25	0.02	12	395	0.36	46	610	386
B290103		0.82	351	29	1.53	76	1200	28	0.04	8	407	0.37	47	570	307
B290104		0.72	358	36	1.47	73	1070	16	0.02	8	394	0.32	39	500	300
B290105		0.66	392	29	1.31	85	950	54	0.02	27	353	0.28	36	590	328
B290106		0.66	322	29	1.32	68	930	37	0.02	16	379	0.26	33	470	286
B290107		0.63	324	35	1.35	56	810	27	0.02	9	384	0.26	33	390	307
B290108		0.53	294	50	1.46	67	800	17	0.07	6	404	0.21	27	430	598
B290109		0.53	226	26	1.40	41	840	24	0.03	9	399	0.22	27	170	739
B290110		0.59	226	22	1.29	42	850	18	0.02	7	361	0.22	28	150	502
B290111		0.97	958	18	1.29	15	430	100	0.14	8	263	0.12	12	40	925
B290112		0.80	644	4	1.40	29	550	45	0.08	7	279	0.19	21	210	199
B290113		0.79	843	17	1.22	32	450	83	0.12	15	233	0.15	17	190	452

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Dat[illegible]-JUN-2005
Account: STRGOL

CERTIFICATE VA05047184

Project: 1735

P.O. No.:

This report is for 45 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 15-JUN-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUN-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05047184

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	K
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	%
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B290114		0.22	0.225	5.2	8.10	5350	1300	3.0	30	1.94	<0.5	16	55	121	3.93	2.72
B290115		0.36	0.356	3.8	7.22	>10000	1330	2.8	20	2.16	<0.5	15	41	93	3.40	3.59
B290116		0.40	0.365	3.6	7.38	6300	1300	2.8	33	2.69	2.5	11	34	108	3.36	3.48
B290117		0.54	0.531	9.3	6.48	8060	870	2.4	29	2.49	2.7	12	30	123	3.29	3.09
B290118		0.58	0.471	9.7	6.57	8280	1040	2.5	30	2.41	2.3	14	28	133	3.33	3.40
B290119		0.94	0.539	10.4	6.99	8390	1300	2.6	19	1.68	<0.5	15	31	136	3.06	4.01
B290120		0.48	0.449	6.4	6.89	6470	1380	2.4	23	2.11	0.5	13	33	109	2.80	4.13
B290121		0.56	0.601	4.4	6.98	8300	1330	2.8	20	2.34	<0.5	13	23	97	2.77	4.12
B290122		1.36	0.685	6.2	6.94	8890	1140	2.8	17	1.98	<0.5	16	52	113	2.81	4.01
B290123		0.52	0.372	2.0	7.04	5430	1220	2.8	41	2.29	<0.5	14	33	72	2.75	3.94
B290124		0.28	0.350	6.8	5.62	7740	740	2.4	16	3.40	2.9	11	26	71	4.42	2.78
B290125		0.70	0.371	13.2	5.37	6530	320	2.1	35	3.02	4.8	13	28	102	5.24	2.67
B290126		0.44	0.229	12.4	6.37	5200	880	2.4	12	1.98	4.6	11	38	114	3.31	3.35
B290127		0.64	0.177	4.8	6.60	5780	1300	2.6	11	1.84	1.0	14	33	82	3.13	3.85
B290128		0.60	0.334	4.1	6.57	9140	1020	2.7	22	1.76	2.1	16	42	83	3.43	3.63
B290129		2.14	0.195	8.4	6.58	4860	1070	2.6	13	2.35	2.7	13	49	117	3.23	3.52
B290130		0.66	0.212	9.5	6.42	5990	290	2.5	20	2.11	6.7	20	72	116	4.94	3.28
B290131		0.70	0.243	11.5	6.52	6330	220	2.6	13	2.21	6.8	21	80	135	5.17	3.19
B290132		0.52	0.252	9.8	6.34	6910	280	2.4	13	2.02	6.6	22	58	116	4.58	3.20
B290133		0.66	0.252	10.6	6.27	7270	180	2.4	19	2.10	6.6	21	66	130	4.70	3.20
B290134		0.28	0.226	17.4	6.32	7550	280	2.4	15	2.13	5.3	23	53	149	4.28	3.21
B290135		0.28	0.196	11.4	6.45	6180	390	2.4	11	2.11	6.3	18	57	128	4.41	3.22
B290136		0.54	0.214	9.8	6.84	5770	1150	2.6	16	2.39	2.8	15	56	119	3.45	3.51
B290137		0.62	0.211	11.8	6.98	5440	1200	2.6	16	2.49	3.1	16	56	126	3.53	3.50
B290138		0.78	0.273	8.6	6.89	5690	1180	2.6	13	2.43	3.1	14	56	121	3.49	3.52
B290139		0.36	0.286	8.5	6.88	6900	1160	2.7	17	2.22	2.5	16	50	111	3.53	3.54
B290140		2.62	0.160	12.0	7.27	4310	1110	3.1	11	2.00	3.0	14	70	135	3.79	3.49
B290141		1.02	0.157	10.4	7.65	4480	1110	3.2	6	1.98	3.4	15	73	136	3.92	3.48
B290142		1.62	0.137	8.2	7.86	3890	1140	3.3	8	2.02	3.2	13	72	129	3.92	3.56
B290143		1.32	0.165	11.0	7.85	3730	1080	3.4	8	1.98	2.9	14	79	132	3.78	3.55
B290144		1.80	0.147	10.8	7.39	4000	1070	3.4	12	1.98	2.6	14	92	133	3.93	3.62
B290145		1.72	0.174	21.7	7.82	5590	1040	3.3	20	2.12	4.0	16	112	177	4.33	3.42
B290146		1.72	0.231	24.6	7.25	8070	840	3.0	25	2.23	5.1	21	105	184	4.48	3.22
B290147		1.06	0.194	11.9	6.49	5400	290	2.6	12	2.17	6.6	17	72	115	4.62	3.08
B290148		1.32	0.196	20.6	7.41	5900	1070	3.2	15	2.24	3.6	17	100	165	4.28	3.47
B290149		0.60	0.163	8.3	6.61	4610	480	2.6	10	2.16	6.4	15	64	104	4.20	3.23
B290150		1.64	0.211	21.6	7.28	7140	1060	3.0	12	2.22	4.0	19	97	163	4.40	3.37
B290151		0.60	0.139	9.1	6.97	4190	370	2.7	10	2.21	4.9	14	63	103	4.19	3.35
B290152		0.52	0.124	8.6	7.12	3500	750	2.7	5	2.12	4.2	13	61	102	3.96	3.47
B290153		0.50	0.408	12.8	6.63	>10000	220	2.7	50	2.05	11.5	27	34	143	4.84	3.26

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUN-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05047184

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B290114		0.81	847	9	1.18	31	760	91	0.28	28	313	0.32	59	80	797
B290115		0.75	407	9	1.12	31	700	61	0.76	29	336	0.27	37	90	120
B290116		0.90	932	9	0.98	26	740	200	0.71	55	338	0.27	36	60	473
B290117		0.85	995	7	0.48	21	680	194	0.60	64	194	0.25	32	110	493
B290118		0.88	769	8	0.41	25	640	160	0.69	52	203	0.25	31	130	490
B290119		0.64	436	7	0.48	27	670	47	0.67	42	217	0.26	34	160	199
B290120		0.64	439	8	0.60	25	730	37	0.70	18	274	0.23	30	90	101
B290121		0.60	349	9	0.94	22	680	34	0.81	15	329	0.22	29	60	55
B290122		0.63	316	7	0.89	30	650	34	0.84	15	315	0.23	30	110	65
B290123		0.81	504	5	1.00	22	730	42	0.58	10	301	0.25	32	60	101
B290124		1.08	2880	6	0.45	18	510	3050	1.20	1375	230	0.20	26	90	494
B290125		1.08	4490	6	0.27	21	550	4640	1.56	2110	192	0.20	26	150	773
B290126		0.77	1620	9	0.24	27	720	1045	0.90	450	168	0.25	32	160	754
B290127		0.71	565	12	0.74	27	750	96	0.66	46	261	0.25	31	80	162
B290128		0.68	627	8	0.81	27	690	158	0.86	39	267	0.25	32	70	373
B290129		0.74	955	10	0.74	52	720	212	0.94	60	273	0.24	30	150	457
B290130		0.84	1130	15	0.33	44	760	214	2.19	44	182	0.23	30	160	1030
B290131		0.84	1175	17	0.33	51	820	252	2.31	50	182	0.25	30	170	1035
B290132		0.80	961	13	0.42	57	690	231	2.04	41	198	0.22	28	200	1000
B290133		0.77	1000	16	0.47	56	770	211	2.16	41	205	0.22	27	200	991
B290134		0.75	925	14	0.55	66	730	192	1.89	54	222	0.23	28	270	839
B290135		0.80	1025	12	0.39	52	760	223	1.93	44	190	0.24	30	190	943
B290136		0.78	1010	10	0.75	47	730	238	1.04	71	279	0.25	32	140	480
B290137		0.81	1110	10	0.72	44	750	296	1.02	90	277	0.25	32	150	498
B290138		0.80	1070	10	0.71	40	750	281	1.01	88	274	0.25	32	120	495
B290139		0.77	947	8	0.71	36	750	291	1.03	96	268	0.25	34	120	425
B290140		0.70	625	20	1.01	42	760	99	0.77	20	318	0.25	39	190	537
B290141		0.73	602	22	1.02	36	790	99	0.73	17	317	0.27	43	210	555
B290142		0.75	601	17	1.06	34	780	85	0.64	16	328	0.28	47	140	515
B290143		0.74	603	16	1.00	37	780	83	0.61	15	315	0.28	47	150	490
B290144		0.76	623	18	0.94	39	800	121	0.66	21	296	0.29	48	190	491
B290145		0.79	707	27	0.82	49	820	144	0.97	23	280	0.27	44	310	706
B290146		0.73	773	32	0.78	57	800	186	1.46	35	267	0.24	37	310	952
B290147		0.81	1130	14	0.34	44	770	235	2.16	40	176	0.24	31	170	999
B290148		0.79	791	33	0.86	49	800	146	1.14	25	290	0.26	38	290	671
B290149		0.80	1055	11	0.42	45	790	244	1.86	37	192	0.24	30	140	964
B290150		0.75	813	31	0.83	52	790	158	1.31	31	273	0.24	34	290	719
B290151		0.82	1060	10	0.41	43	800	204	1.82	43	190	0.26	33	140	810
B290152		0.81	991	12	0.43	38	830	195	1.60	29	194	0.26	34	130	738
B290153		0.66	729	18	0.83	51	710	313	2.43	33	271	0.20	25	190	1660

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUN-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05047184

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290154		0.64	0.235	8.4	7.49	5040	990	3.3	9	1.96	6.3	16	58	123	4.23	3.56
B290155		0.72	0.218	6.2	7.86	5120	1080	3.3	13	2.13	7.3	16	58	139	4.50	3.50
B290156		0.76	0.222	5.2	7.50	6140	1080	3.4	12	2.15	6.3	17	64	123	4.46	3.63
B290157		0.98	0.290	7.8	8.30	9650	740	3.5	16	2.25	8.7	26	66	131	5.33	3.61
B290158		1.06	0.299	5.3	7.63	>10000	720	3.4	19	2.00	8.3	25	66	142	5.29	3.78

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUN-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05047184

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B290154		0.96	610	12	1.07	35	760	169	1.48	25	309	0.27	39	100	980
B290155		0.97	628	11	1.10	34	690	193	1.83	30	337	0.27	38	90	1060
B290156		0.92	624	14	1.07	29	750	177	1.77	24	330	0.28	39	80	950
B290157		0.92	707	13	0.86	40	860	243	2.58	40	286	0.31	42	100	1260
B290158		0.86	653	12	0.89	38	840	231	2.51	33	288	0.29	39	90	1220

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da .7-JUN-2005
Account: STRGOL

CERTIFICATE VA05047826

Project: Dublin Gulch-1735

P.O. No.:

This report is for 40 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 17-JUN-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 27-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047826

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290159		1.98	0.490	8.2	5.84	>10000	70	2.3	44	2.69	21.1	30	92	420	6.50	3.00
B290160		0.98	0.455	12.8	5.64	>10000	140	2.2	41	2.74	16.3	29	107	571	6.50	2.92
B290161		1.38	0.499	22.6	6.32	>10000	150	2.6	41	2.43	21.5	29	108	447	7.60	2.91
B290162		0.74	0.479	18.5	6.33	>10000	100	2.7	37	2.39	20.6	32	124	411	8.13	3.05
B290163		0.98	0.686	17.1	5.85	>10000	200	2.3	41	2.42	17.4	35	103	334	8.19	2.94
B290164		0.78	0.681	17.2	5.58	>10000	80	2.2	43	2.36	14.2	40	96	346	7.95	3.05
B290165		1.06	0.712	19.0	5.77	>10000	140	2.3	43	2.30	15.6	44	118	411	8.59	2.94
B290166		0.94	0.578	15.2	6.52	>10000	80	2.7	40	2.36	16.9	36	98	383	8.11	3.22
B290167		1.14	0.393	3.8	6.36	9930	220	2.6	36	2.42	8.6	25	82	186	5.62	3.38
B290168		0.94	0.477	6.5	6.44	>10000	200	2.5	34	2.46	13.0	34	91	271	7.01	3.42
B290169		1.06	0.590	9.1	6.29	>10000	140	2.6	35	2.42	16.2	40	101	336	7.86	3.32
B290170		1.18	0.295	2.4	6.87	7730	1200	2.7	22	2.35	3.2	19	70	138	4.74	3.62
B290171		0.86	0.358	7.0	6.69	9650	250	2.7	24	2.36	5.3	23	70	198	5.19	3.53
B290172		0.58	0.338	7.1	6.61	9090	330	2.7	23	2.41	7.8	24	97	208	5.75	3.39
B290173		0.74	0.406	8.5	6.38	>10000	310	2.6	25	2.23	10.6	25	84	226	5.68	3.29
B290174		1.46	0.434	7.6	6.99	>10000	200	2.9	30	2.36	15.7	26	80	254	6.67	3.39
B290175		0.56	0.335	3.9	6.90	6560	290	2.9	18	2.03	11.6	18	59	146	4.91	3.38
B290176		0.68	0.336	5.5	6.92	6290	580	2.8	22	2.11	7.4	17	76	151	4.76	3.48
B290177		1.94	0.271	3.6	6.71	6440	600	2.6	16	2.20	5.7	15	75	148	4.56	3.52
B290178		0.52	0.384	3.6	7.44	6240	640	2.9	20	2.29	7.3	15	83	141	4.96	3.74
B290179		0.76	0.238	2.0	6.41	5090	650	2.4	12	2.20	6.3	10	67	151	4.21	3.43
B290180		0.48	0.339	3.9	6.07	6540	310	2.3	14	2.22	9.7	14	65	184	4.65	3.13
B290181		0.42	0.256	2.9	6.00	5580	320	2.2	20	2.17	8.1	12	63	172	4.29	3.30
B290182		0.26	0.484	4.2	5.66	>10000	160	2.1	20	2.29	13.4	22	49	207	5.74	2.99
B290183		0.86	0.257	2.2	6.63	5430	380	2.5	14	2.06	5.9	14	72	137	4.68	3.33
B290184		0.62	0.294	3.3	6.91	5880	510	2.6	15	2.18	6.7	13	67	149	4.78	3.54
B290185		0.14	NSS	6.5	6.05	7130	260	2.3	25	2.20	10.9	14	56	170	4.58	3.15
B290186		0.34	0.287	6.8	7.09	6070	680	2.8	22	2.10	8.7	28	77	152	5.31	3.32
B290187		0.28	0.343	5.1	6.97	5980	250	2.9	23	2.09	14.9	15	71	186	5.70	3.30
B290188		0.32	0.308	7.6	6.76	6300	270	2.8	19	2.06	12.2	16	70	168	5.46	3.19
B290189		0.26	0.319	5.3	6.70	5310	420	2.7	16	2.13	12.0	15	59	161	5.27	3.31
B290190		0.48	0.351	4.2	6.58	6650	380	2.5	20	2.21	10.1	17	73	177	5.78	3.19
B290191		0.72	0.228	7.5	6.57	7090	520	2.6	21	2.32	7.2	16	73	154	4.32	3.48
B290192		0.56	0.350	7.3	6.01	7860	290	2.4	27	2.14	8.9	18	59	164	4.76	3.05
B290193		0.48	0.286	3.4	6.42	6080	280	2.4	22	2.18	9.0	15	72	154	5.12	3.25
B290194		0.80	0.295	3.5	6.00	6130	200	2.3	15	2.04	7.7	14	69	144	4.94	3.04
B290195		0.36	0.264	3.6	6.59	5380	290	2.5	12	2.16	8.5	13	65	151	4.83	3.37
B290196		0.48	0.273	4.2	6.37	4970	400	2.4	14	2.19	9.4	12	72	148	5.10	3.20
B290197		0.40	0.325	4.8	6.02	5820	480	2.3	10	2.09	8.6	14	70	148	4.77	3.12
B290198		0.40	0.343	3.9	5.71	6880	220	2.2	16	2.08	10.0	15	66	164	4.85	3.03

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 27-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047826

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B290159		0.74	964	9	0.56	71	720	491	4.21	51	229	0.19	24	960	3080
B290160		0.71	1005	33	0.65	78	680	307	3.30	39	256	0.19	25	1430	2500
B290161		0.78	1015	63	0.52	77	720	441	4.17	53	209	0.22	29	1230	3060
B290162		0.80	1040	75	0.55	70	710	429	3.97	43	223	0.23	32	1110	2910
B290163		0.70	1070	52	0.67	79	700	398	3.69	57	253	0.21	26	740	2600
B290164		0.62	990	55	0.77	78	660	330	3.63	67	268	0.18	23	770	2210
B290165		0.66	966	67	0.73	105	760	426	4.01	68	262	0.20	26	1140	2480
B290166		0.78	958	51	0.69	74	770	390	4.00	65	254	0.24	31	910	2610
B290167		0.70	758	16	0.99	55	660	221	2.38	45	328	0.19	25	360	1360
B290168		0.70	900	29	0.90	63	710	254	3.15	45	307	0.20	26	520	1915
B290169		0.71	923	40	0.81	80	780	388	3.78	56	284	0.22	28	730	2470
B290170		0.71	547	16	1.18	44	680	150	1.42	25	367	0.21	29	260	575
B290171		0.69	612	24	1.12	47	730	210	1.88	38	348	0.21	28	380	809
B290172		0.74	736	26	1.00	60	690	219	2.08	33	327	0.22	29	460	1240
B290173		0.70	724	29	0.82	54	730	308	2.55	44	278	0.21	28	470	1645
B290174		0.81	823	22	0.69	57	840	424	3.59	47	256	0.24	32	490	2280
B290175		0.76	627	14	0.59	36	750	266	2.41	33	230	0.23	31	250	1630
B290176		0.77	616	15	0.72	36	750	209	1.80	36	266	0.24	34	250	1175
B290177		0.72	587	16	0.81	41	780	169	1.57	26	289	0.22	30	290	935
B290178		0.82	671	18	0.76	44	800	195	1.74	40	292	0.25	35	260	1140
B290179		0.72	650	10	0.70	34	720	234	1.66	55	269	0.22	29	250	1065
B290180		0.64	691	12	0.68	40	710	242	2.18	42	253	0.20	24	370	1440
B290181		0.66	644	10	0.71	33	740	222	1.97	56	265	0.20	25	310	1215
B290182		0.62	750	12	0.62	46	800	350	3.48	82	241	0.19	22	400	1975
B290183		0.73	637	14	0.66	31	760	255	1.86	75	258	0.23	31	240	1060
B290184		0.77	680	14	0.69	30	760	277	1.98	77	269	0.22	31	280	1160
B290185		0.69	722	12	0.63	41	580	304	2.27	54	241	0.19	26	300	1670
B290186		0.81	681	17	0.69	36	770	241	2.16	49	253	0.26	38	210	1290
B290187		0.82	790	15	0.50	44	730	355	3.07	72	207	0.24	35	290	2180
B290188		0.79	733	15	0.58	35	730	334	2.72	56	226	0.24	33	290	1815
B290189		0.78	747	14	0.57	34	700	368	2.59	57	229	0.24	33	330	1900
B290190		0.74	823	18	0.63	44	740	407	2.58	112	242	0.23	29	340	1510
B290191		0.68	709	15	0.91	45	750	185	1.61	30	302	0.20	27	310	1175
B290192		0.67	737	14	0.69	40	710	290	2.05	64	246	0.20	27	310	1395
B290193		0.73	779	14	0.61	38	710	389	2.32	108	241	0.22	29	270	1425
B290194		0.69	738	13	0.58	34	660	329	2.17	96	227	0.19	27	240	1245
B290195		0.74	760	13	0.64	35	720	352	2.18	110	248	0.22	29	270	1365
B290196		0.71	862	17	0.65	35	690	370	2.06	110	235	0.22	28	260	1415
B290197		0.66	773	16	0.70	36	600	377	2.01	122	246	0.20	25	270	1285
B290198		0.66	780	14	0.62	29	640	380	2.27	102	231	0.20	25	290	1555

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 1-JUL-2005
Account: STRGOL

CERTIFICATE VA05048596

Project: Dublin Gulch-1735

P.O. No.:

This report is for 127 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 20-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Method / Analyte / Units / LOR / Sample Description	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290199	1.16	0.292	3.5	6.57	8410	430	2.6	22	2.10	6.7	16	69	164	4.23	3.56
B290200	3.04	0.277	>100	4.93	575	1530	1.3	10	0.40	1.0	9	231	432	3.49	1.69
B290201	1.06	0.174	75.3	3.57	545	900	0.9	3	0.27	0.8	6	246	311	3.31	1.23
B290202	1.40	0.062	39.6	3.83	605	640	1.0	<2	0.24	1.1	4	199	164	2.90	1.28
B290203	3.00	0.245	24.9	4.67	630	750	1.3	8	0.22	1.6	6	100	129	2.88	1.66
B290204	0.96	0.326	21.1	5.35	589	800	1.5	6	0.24	1.0	4	85	100	2.95	2.01
B290205	0.18	NSS	21.4	5.17	368	610	1.3	5	0.35	0.6	4	63	110	2.46	1.50
B290206	0.36	0.130	14.2	8.43	499	1020	2.1	6	0.35	<0.5	3	100	83	4.46	2.85
B290207	0.94	0.486	22.4	6.00	564	850	1.8	12	0.42	2.0	9	86	117	3.20	2.26
B290208	2.66	0.556	23.0	6.88	951	1290	2.3	12	0.68	3.5	18	82	168	3.58	2.79
B290209	2.48	0.918	20.2	6.93	841	3020	2.2	15	0.87	1.3	7	79	143	3.57	2.85
B290210	1.62	0.960	21.8	6.53	730	1320	2.0	11	0.44	2.1	9	107	124	3.57	2.75
B290211	2.26	0.769	15.3	6.46	1090	1980	2.2	30	0.79	0.6	7	70	115	3.31	2.68
B290212	2.04	0.743	8.7	7.15	724	2590	2.4	15	1.29	0.5	7	77	79	2.93	2.89
B290213	2.38	1.590	17.3	6.38	587	1980	2.4	8	1.40	<0.5	9	112	125	2.56	2.84
B290214	3.22	0.460	31.1	6.38	756	1860	2.2	8	1.38	<0.5	9	75	159	2.55	2.70
B290215	2.82	0.936	18.6	5.97	682	1340	2.0	13	0.92	<0.5	9	58	115	2.33	2.72
B290216	2.64	2.27	14.6	5.98	509	1260	1.9	8	0.97	<0.5	6	60	100	2.52	2.21
B290217	1.50	1.320	28.0	7.36	352	1440	2.5	13	1.68	<0.5	7	64	218	2.77	3.03
B290218	1.70	1.045	28.6	6.53	575	1360	2.1	13	1.46	<0.5	12	73	242	2.91	2.88
B290219	1.26	1.060	20.2	6.68	629	1120	2.0	19	1.57	<0.5	8	84	129	3.23	2.55
B290220	1.14	0.934	10.3	7.08	870	1140	2.4	27	1.64	<0.5	8	83	116	3.08	2.82
B290221	0.48	1.100	10.3	6.24	633	980	1.9	33	1.28	<0.5	13	98	124	3.67	2.12
B290222	0.84	5.65	20.4	5.31	756	810	1.7	151	1.06	<0.5	11	103	160	3.55	1.92
B290223	0.96	1.480	24.1	6.29	639	890	2.0	29	1.29	<0.5	8	145	148	4.19	2.54
B290224	1.24	0.642	7.5	6.44	498	880	2.0	8	1.04	<0.5	7	68	70	3.13	2.27
B290225	0.86	2.48	13.9	6.14	808	900	1.9	20	0.98	0.9	11	127	109	4.07	2.39
B290226	0.46	0.805	4.8	6.93	601	1020	2.1	19	1.04	<0.5	14	100	68	3.46	2.50
B290227	0.50	0.628	7.9	6.92	774	1000	2.1	20	1.14	<0.5	10	98	80	3.30	2.66
B290228	1.44	0.262	3.7	6.75	779	1100	2.1	15	1.26	<0.5	9	77	68	2.97	2.51
B290229	1.38	1.020	3.3	6.61	597	920	1.9	7	1.11	<0.5	8	67	52	2.89	2.38
B290230	0.76	4.05	6.4	6.86	938	1110	2.0	37	1.28	0.7	16	62	91	3.32	2.83
B290231	0.66	3.17	12.1	6.56	1655	1390	2.2	22	1.36	<0.5	28	46	138	2.54	3.60
B290232	0.58	1.850	10.3	6.75	871	1430	2.4	31	1.36	<0.5	17	48	120	2.38	3.54
B290233	1.00	1.925	10.6	6.75	549	1480	2.2	32	1.69	<0.5	15	50	97	2.18	3.59
B290234	1.38	2.63	12.6	6.43	833	1390	2.0	27	1.59	<0.5	15	65	120	2.46	3.44
B290235	0.52	1.735	9.2	6.47	668	1360	2.4	38	1.44	<0.5	13	53	87	2.42	3.43
B290236	1.04	2.19	10.1	5.93	847	1350	1.9	18	1.35	<0.5	13	51	81	2.09	3.39
B290237	0.88	2.84	9.4	6.39	1045	1380	2.1	21	1.56	<0.5	18	51	117	2.50	3.70
B290238	1.40	1.495	25.5	6.85	723	1370	2.6	27	1.58	<0.5	15	56	152	2.64	3.53

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290199		0.70	584	14	0.88	33	620	152	1.70	29	290	0.21	29	260	1065	
B290200		0.33	1025	17	0.34	55	300	99	0.02	74	89	0.14	28	1190	309	119
B290201		0.24	1055	22	0.19	49	210	84	0.02	71	54	0.10	20	730	311	
B290202		0.23	957	19	0.14	33	180	117	0.02	75	45	0.14	25	490	309	
B290203		0.24	808	17	0.13	29	250	180	0.02	104	48	0.19	35	270	364	
B290204		0.27	495	20	0.16	18	260	560	0.06	238	59	0.21	42	230	425	
B290205		0.35	431	10	0.27	16	240	205	0.08	116	71	0.16	32	300	320	
B290206		0.45	398	12	0.28	18	380	592	0.38	285	105	0.28	66	180	679	
B290207		0.44	473	13	0.36	20	350	555	0.15	276	129	0.18	32	270	579	
B290208		0.51	477	18	0.66	33	530	340	0.11	159	182	0.20	33	230	685	
B290209		0.44	462	17	0.57	29	540	516	0.16	164	200	0.21	34	190	411	
B290210		0.44	347	20	0.38	21	380	695	0.21	261	160	0.22	39	150	685	
B290211		0.44	401	9	0.60	22	530	362	0.17	134	194	0.22	33	170	340	
B290212		0.54	365	16	0.94	22	470	237	0.14	95	297	0.17	31	100	290	
B290213		0.49	284	21	0.95	22	510	181	0.06	47	276	0.15	22	210	144	
B290214		0.44	287	13	0.95	24	520	169	0.07	56	281	0.16	23	330	166	
B290215		0.35	249	15	0.81	18	480	220	0.08	66	227	0.14	23	170	188	
B290216		0.48	388	13	0.76	17	440	122	0.05	48	207	0.15	23	180	150	
B290217		0.66	499	13	1.17	30	540	116	0.04	29	322	0.19	25	320	87	
B290218		0.54	379	19	0.91	29	510	168	0.06	37	273	0.16	22	350	94	
B290219		0.58	476	21	0.81	24	470	193	0.07	54	238	0.17	24	240	126	
B290220		0.61	404	15	0.95	20	560	91	0.07	31	262	0.19	26	180	126	
B290221		0.58	430	27	0.81	20	430	163	0.09	42	230	0.16	23	200	110	
B290222		0.45	453	29	0.61	32	300	150	0.10	47	180	0.14	22	310	130	
B290223		0.45	554	37	0.70	27	450	186	0.07	74	199	0.14	27	280	193	
B290224		0.47	653	17	0.73	20	420	167	0.08	75	176	0.17	26	100	194	
B290225		0.45	802	35	0.66	26	370	203	0.09	89	196	0.17	29	160	265	
B290226		0.59	512	23	0.82	19	410	186	0.08	87	219	0.19	30	90	222	
B290227		0.58	451	23	0.95	19	420	187	0.09	87	237	0.19	29	130	196	
B290228		0.60	423	16	0.97	17	420	93	0.15	57	249	0.19	27	80	148	
B290229		0.50	459	16	0.84	14	340	112	0.15	63	212	0.17	27	50	168	
B290230		0.54	603	13	0.74	22	490	156	0.19	91	209	0.22	33	100	261	
B290231		0.57	261	11	0.90	22	540	79	0.20	44	268	0.21	28	190	89	
B290232		0.61	226	7	1.10	23	570	50	0.12	28	292	0.22	29	170	73	
B290233		0.60	245	8	1.06	21	600	47	0.07	22	307	0.21	28	160	79	
B290234		0.52	270	11	0.73	25	600	68	0.15	35	254	0.21	27	200	168	
B290235		0.51	275	9	0.91	22	550	62	0.12	28	260	0.22	28	140	87	
B290236		0.47	266	9	0.82	20	540	87	0.11	25	262	0.17	23	170	82	
B290237		0.60	281	10	0.77	24	500	94	0.24	32	279	0.20	28	180	89	
B290238		0.63	312	10	1.17	27	600	111	0.18	50	331	0.24	33	310	110	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290239		4.52	1.625	>100	6.94	832	4760	2.4	12	1.24	<0.5	12	59	324	2.67	3.19
B290240		1.80	0.974	90.9	6.97	1180	3410	2.4	22	1.48	<0.5	12	45	217	2.30	3.34
B290241		2.88	0.717	83.0	6.88	1185	3910	2.6	14	1.64	<0.5	13	53	214	2.34	3.34
B290242		1.14	0.686	78.0	7.05	1005	2160	2.6	10	1.80	<0.5	11	44	158	2.20	2.97
B290243		1.34	0.901	91.5	6.32	1220	2700	2.3	11	1.74	<0.5	10	46	209	2.16	3.28
B290244		1.70	0.634	58.3	6.79	1155	1940	2.6	18	1.80	<0.5	10	46	142	2.24	3.32
B290245		0.60	0.941	79.5	6.63	1300	1700	2.4	18	1.68	<0.5	11	48	193	2.29	3.40
B290246		1.08	0.533	57.8	6.53	1670	1730	2.4	13	1.65	<0.5	15	44	170	2.34	3.32
B290247		1.14	1.350	49.1	6.49	1705	1750	2.5	27	1.76	<0.5	15	45	140	2.26	3.49
B290248		1.26	0.704	64.8	6.20	1605	1260	2.4	21	1.60	1.9	9	55	169	2.47	3.11
B290249		0.72	0.557	60.9	6.77	1745	1600	2.9	16	1.81	<0.5	17	52	154	2.30	3.50
B290250		0.88	0.906	53.7	6.81	1175	1740	2.6	13	1.84	<0.5	14	56	182	2.45	3.39
B290251		0.76	0.712	46.5	6.45	809	1770	2.3	13	1.96	<0.5	11	56	141	2.13	3.49
B290252		0.70	0.981	37.8	5.95	930	1520	2.0	34	2.39	<0.5	13	58	126	2.01	2.88
B290253		0.62	1.035	41.1	6.32	690	1160	2.2	34	2.00	<0.5	13	58	134	2.45	2.86
B290254		0.54	0.983	28.2	6.33	558	1430	2.4	26	1.56	<0.5	11	52	98	2.35	3.17
B290255		0.92	1.130	40.7	5.64	527	1190	2.2	6	1.94	<0.5	9	48	103	2.52	2.73
B290256		0.52	0.780	41.3	5.65	1460	940	2.1	16	1.62	1.0	10	54	138	2.83	2.69
B290257		0.84	0.652	47.9	6.56	1025	1530	2.5	9	1.75	<0.5	11	62	128	2.67	3.60
B290258		0.78	0.602	40.9	6.32	1210	1180	2.1	18	1.52	<0.5	10	62	124	2.76	3.22
B290259		0.76	1.080	21.2	5.38	1215	1330	1.7	19	0.95	<0.5	12	59	84	2.44	3.24
B290260		1.24	0.926	22.5	5.66	705	1240	1.9	8	1.48	<0.5	9	41	60	2.16	2.91
B290261		0.86	0.991	22.2	5.30	581	1240	1.7	16	1.64	0.5	10	51	67	2.34	2.86
B290262		0.84	0.742	75.2	5.91	696	1280	1.9	11	1.86	0.6	10	56	155	2.58	3.43
B290263		1.38	1.245	>100	5.53	324	1280	1.8	25	1.60	1.2	9	55	513	2.68	3.05
B290264		3.00	0.704	>100	5.90	838	1260	2.0	14	1.50	0.6	11	70	492	2.88	3.32
B290265		10.12	1.155	>100	6.23	774	1100	2.1	19	1.72	0.6	11	99	264	3.81	3.04
B290266		0.44	0.231	7.0	6.90	2470	1420	2.9	9	2.58	<0.5	8	64	84	2.71	3.76
B290267		0.16	0.218	13.8	7.07	2730	1330	3.1	8	2.98	<0.5	8	88	114	3.17	3.52
B290268		0.30	0.231	15.6	7.15	2860	1380	3.2	7	2.94	<0.5	8	105	137	3.34	3.48
B290269		0.20	0.206	26.4	7.12	2420	1240	3.2	6	2.95	<0.5	8	103	172	3.22	3.41
B290270		0.20	0.192	9.0	6.97	2710	1390	3.1	9	2.90	<0.5	7	85	97	2.98	3.69
B290271		0.30	0.269	10.4	7.21	2780	1420	3.2	8	2.96	<0.5	7	89	101	3.22	3.57
B290272		0.16	0.226	29.7	7.18	2820	1300	3.2	11	3.02	<0.5	8	91	182	3.11	3.51
B290273		0.20	0.190	34.5	7.58	2430	1280	3.3	7	3.16	<0.5	8	134	226	3.36	3.59
B290274		0.34	0.189	24.5	7.42	2460	1280	3.3	8	3.15	<0.5	8	106	166	3.23	3.62
B290275		0.20	0.203	13.7	7.37	3060	1320	3.2	11	3.33	<0.5	9	86	120	3.18	3.66
B290276		0.26	0.162	6.2	6.83	3220	1310	2.8	13	2.55	<0.5	13	137	111	3.16	3.83
B290277		0.40	0.208	6.8	6.92	3590	1280	2.9	9	2.55	<0.5	12	157	106	3.30	3.83
B290278		0.34	0.282	6.9	6.23	5370	840	2.5	8	2.29	<0.5	17	162	108	3.41	3.59

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290239		0.56	288	8	0.84	53	520	185	0.16	82	292	0.25	36	660	229	133
B290240		0.55	214	6	1.06	50	550	180	0.26	73	340	0.24	33	500	146	
B290241		0.59	224	9	1.06	42	600	157	0.24	50	338	0.23	32	450	113	
B290242		0.56	204	6	1.36	41	630	79	0.26	27	384	0.21	27	380	62	
B290243		0.50	232	9	0.97	44	590	122	0.35	42	307	0.21	27	440	93	
B290244		0.56	260	7	1.25	41	590	87	0.27	34	344	0.23	29	280	78	
B290245		0.59	219	8	1.12	46	580	89	0.25	36	330	0.23	30	420	73	
B290246		0.60	215	8	1.06	40	570	117	0.44	41	315	0.22	29	310	84	
B290247		0.53	210	8	1.18	36	550	133	0.38	50	353	0.21	27	250	240	
B290248		0.52	407	7	0.43	36	630	318	0.79	89	177	0.22	29	300	388	
B290249		0.60	224	6	1.33	42	550	99	0.26	30	375	0.24	33	320	108	
B290250		0.55	223	8	1.21	39	580	91	0.37	28	346	0.23	30	310	85	
B290251		0.42	228	8	0.98	30	600	91	0.23	30	281	0.23	29	270	75	
B290252		0.41	281	10	1.00	28	580	81	0.32	37	245	0.20	26	230	73	
B290253		0.55	234	9	1.10	32	590	120	0.37	53	286	0.22	31	250	88	
B290254		0.47	209	10	0.94	30	560	104	0.18	35	291	0.22	30	180	84	
B290255		0.57	428	6	0.57	28	550	152	0.55	54	233	0.20	28	240	190	
B290256		0.57	390	11	0.52	30	540	277	0.86	104	194	0.20	29	250	319	
B290257		0.50	329	10	0.85	30	630	120	0.35	46	274	0.22	32	260	104	
B290258		0.58	307	11	0.46	30	610	234	0.61	88	206	0.23	31	250	214	
B290259		0.35	228	14	0.45	29	530	211	0.46	67	189	0.17	23	140	148	
B290260		0.40	264	8	0.76	24	570	173	0.32	55	236	0.18	24	120	134	
B290261		0.46	318	10	0.57	22	610	185	0.43	53	212	0.18	25	120	268	
B290262		0.50	338	12	0.48	42	630	213	0.37	98	215	0.19	25	350	212	
B290263		0.43	356	11	0.43	80	650	192	0.57	70	185	0.20	26	850	343	337
B290264		0.50	351	13	0.42	67	640	154	0.50	54	183	0.21	28	920	230	326
B290265		0.53	437	19	0.40	58	580	217	0.42	94	178	0.21	35	510	321	163
B290266		0.87	243	6	1.40	28	440	22	0.70	8	348	0.19	28	100	29	
B290267		0.77	273	9	1.35	39	520	24	0.80	6	405	0.21	31	200	32	
B290268		0.76	275	8	1.35	48	600	30	0.85	11	408	0.22	32	220	31	
B290269		0.81	271	10	1.37	50	570	25	0.65	8	417	0.22	34	360	31	
B290270		0.79	256	6	1.41	36	510	26	0.78	5	397	0.20	30	150	28	
B290271		0.80	270	6	1.38	33	560	25	0.84	7	405	0.21	32	160	29	
B290272		0.74	265	8	1.37	49	540	33	0.76	10	417	0.21	32	380	40	
B290273		0.84	286	11	1.46	65	620	29	0.68	12	439	0.23	36	440	40	
B290274		0.83	276	10	1.46	54	620	23	0.67	7	439	0.23	35	320	29	
B290275		0.76	270	8	1.45	50	550	23	0.82	8	439	0.21	31	240	25	
B290276		0.63	480	7	0.95	31	640	94	0.95	45	313	0.20	26	90	182	
B290277		0.64	481	7	0.94	31	650	91	1.05	42	313	0.20	25	100	166	
B290278		0.55	431	7	0.89	33	640	82	1.30	40	292	0.17	22	90	154	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290279		0.38	0.243	9.4	6.61	4010	1280	2.8	7	2.42	1.1	14	141	128	3.34	3.73
B290280		0.44	0.123	3.3	6.87	2150	1300	2.8	7	2.37	<0.5	9	135	69	2.74	3.80
B290281		0.50	0.173	4.3	6.54	3060	1280	2.7	7	2.51	0.9	11	157	100	2.89	3.73
B290282		0.32	0.339	16.5	6.21	8350	470	2.5	16	2.44	1.1	23	138	174	3.86	3.52
B290283		0.32	0.501	16.0	6.10	>10000	180	2.6	22	2.31	2.0	32	190	203	4.90	3.46
B290284		0.38	0.395	19.9	6.68	6050	490	2.8	16	2.54	0.8	16	180	175	3.73	3.61
B290285		0.34	0.449	16.3	6.22	8590	480	2.6	18	2.44	1.1	24	200	177	4.07	3.52
B290286		0.40	0.417	18.2	6.28	6590	460	2.6	15	2.39	1.4	18	178	173	3.91	3.36
B290287		0.52	0.233	16.2	6.78	3590	950	2.8	12	2.55	0.5	11	136	141	3.09	3.63
B290288		0.48	0.300	19.5	6.82	4630	1280	2.9	13	2.35	0.5	13	118	152	3.36	3.52
B290289		0.58	0.417	20.1	6.62	6880	800	2.8	19	2.42	1.0	20	150	196	3.96	3.60
B290290		0.40	0.916	27.8	6.32	>10000	140	2.7	29	2.32	1.2	30	146	230	5.45	3.47
B290291		0.34	0.424	24.1	6.17	8550	320	2.5	13	2.25	5.7	16	60	170	3.98	3.41
B290292		0.28	0.521	30.8	6.38	>10000	400	2.6	16	2.43	3.6	20	85	212	4.53	3.48
B290293		0.30	0.691	41.6	6.19	>10000	200	2.5	26	2.29	1.7	29	143	252	4.66	3.58
B290294		0.28	0.591	24.0	6.20	9780	190	2.6	15	2.27	5.5	16	81	181	4.83	3.35
B290295		0.30	0.886	24.3	5.70	>10000	160	2.3	40	2.28	6.8	33	95	211	6.95	3.20
B290296		0.38	0.524	28.8	6.03	>10000	80	2.6	16	2.23	8.7	20	93	213	5.74	3.14
B290297		0.38	0.516	22.3	6.12	>10000	160	2.6	13	2.20	7.7	16	98	182	5.39	3.08
B290298		0.44	0.707	17.5	5.62	>10000	90	2.2	25	2.08	8.2	23	69	172	5.55	3.07
B290299		0.42	0.703	17.6	5.20	>10000	70	2.0	31	2.04	10.4	24	59	181	5.38	2.95
B290300		0.38	0.709	25.9	5.70	>10000	70	2.3	32	2.03	6.1	35	66	210	6.15	3.07
B290301		0.30	0.683	18.5	5.86	>10000	120	2.2	22	1.98	6.0	24	73	179	5.13	3.26
B290302		0.26	0.684	17.4	5.65	>10000	140	2.1	24	1.92	6.9	24	58	179	5.36	3.10
B290303		0.48	0.570	17.4	6.80	>10000	320	2.7	26	2.39	2.0	24	85	169	4.61	3.48
B290304		0.28	0.963	27.7	5.84	>10000	90	2.3	27	2.12	5.9	35	92	232	6.45	3.15
B290305		0.38	0.740	28.2	5.86	>10000	110	2.3	34	2.11	4.7	32	93	208	6.00	3.08
B290306		0.34	0.983	29.5	5.45	>10000	120	2.1	41	1.96	8.1	39	73	244	7.12	3.04
B290307		0.30	0.855	24.7	5.94	>10000	110	2.3	29	2.04	6.5	29	67	204	5.87	3.24
B290308		0.34	0.446	12.6	6.63	9340	190	2.6	16	2.24	2.6	22	69	165	4.30	3.50
B290309		0.32	0.366	21.0	6.64	6230	390	2.5	16	2.16	1.6	18	90	166	3.40	3.58
B290310		0.40	0.361	12.8	6.66	6870	360	2.6	13	2.22	2.5	16	78	133	3.61	3.48
B290311		0.46	0.282	8.7	6.78	4940	720	2.6	12	2.24	1.5	10	58	123	3.05	3.62
B290312		0.32	0.298	6.7	6.86	5610	820	2.7	16	2.28	0.7	12	65	116	3.17	3.67
B290313		0.36	0.281	10.2	6.98	4440	750	2.7	10	2.17	1.8	11	55	110	3.10	3.65
B290314		0.28	0.215	11.4	7.55	3180	1580	2.9	11	2.24	0.9	9	66	99	2.98	3.88
B290315		0.32	0.157	9.6	7.89	2450	1810	3.1	7	2.15	1.6	7	63	90	3.15	3.94
B290316		0.38	0.219	9.8	7.38	3110	1550	2.8	8	2.16	1.6	9	55	94	2.99	3.87
B290317		0.42	0.330	9.3	7.27	4930	880	2.8	12	2.38	1.1	13	62	126	3.20	3.85
B290318		0.38	0.302	13.0	7.28	5090	740	2.8	11	2.18	2.9	11	57	118	3.46	3.80

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290279		0.60	454	6	0.91	33	710	89	1.23	35	300	0.19	23	130	215	
B290280		0.64	433	5	0.96	25	660	72	0.71	32	310	0.19	25	70	118	
B290281		0.57	473	5	0.91	28	650	80	0.92	38	302	0.18	23	90	210	
B290282		0.56	456	5	0.85	46	730	135	1.71	60	287	0.17	21	230	273	
B290283		0.52	459	6	0.79	53	770	190	2.54	92	266	0.18	21	230	435	
B290284		0.65	461	7	0.95	40	740	126	1.42	65	305	0.20	24	260	246	
B290285		0.55	489	7	0.82	44	730	142	1.74	67	280	0.18	22	240	286	
B290286		0.60	487	9	0.91	42	720	135	1.53	68	288	0.19	25	240	275	
B290287		0.66	463	7	1.08	35	730	128	0.99	55	336	0.20	25	170	201	
B290288		0.70	418	7	1.15	41	730	116	1.09	55	353	0.23	29	210	195	
B290289		0.60	443	8	1.03	50	770	152	1.53	70	319	0.20	24	250	247	
B290290		0.54	478	14	1.06	58	720	215	2.57	101	315	0.19	22	330	303	
B290291		0.55	415	6	0.95	35	700	293	1.91	93	296	0.19	23	240	872	
B290292		0.58	415	11	1.02	45	800	230	2.06	86	315	0.19	23	350	651	
B290293		0.53	416	8	0.97	54	870	184	2.29	78	302	0.19	21	460	332	
B290294		0.60	504	9	0.90	38	760	366	2.47	114	294	0.20	24	260	926	
B290295		0.51	498	14	0.89	51	720	583	4.20	178	290	0.18	21	270	1095	
B290296		0.62	568	12	0.80	41	860	487	3.29	148	264	0.20	25	280	1350	
B290297		0.66	579	11	0.80	39	760	462	2.98	145	269	0.20	26	220	1275	
B290298		0.48	530	9	0.82	39	720	403	3.40	142	273	0.18	19	180	1280	
B290299		0.45	558	7	0.76	38	810	482	3.57	156	258	0.18	17	160	1590	
B290300		0.47	386	8	0.93	51	740	356	3.87	131	282	0.18	19	270	974	
B290301		0.48	448	8	0.91	37	660	374	3.08	136	287	0.18	19	190	932	
B290302		0.46	431	9	0.87	44	630	370	3.33	119	276	0.18	19	170	1045	
B290303		0.54	326	8	1.23	45	810	173	2.28	76	359	0.19	21	200	330	
B290304		0.50	445	12	0.95	53	740	419	3.90	136	290	0.19	21	280	899	
B290305		0.50	397	9	0.98	52	740	344	3.51	121	293	0.19	20	270	722	
B290306		0.44	450	12	0.87	58	760	562	4.77	187	272	0.19	19	300	1285	
B290307		0.47	469	9	0.94	47	840	433	3.78	143	293	0.20	19	250	1015	
B290308		0.54	363	9	1.13	39	720	200	2.14	80	336	0.19	21	170	403	
B290309		0.54	377	6	1.08	36	720	152	1.46	56	331	0.18	20	200	294	
B290310		0.56	353	7	1.13	31	730	177	1.62	65	342	0.19	21	160	380	
B290311		0.58	273	6	1.22	25	670	111	1.20	41	357	0.19	22	110	236	
B290312		0.61	228	8	1.21	25	620	70	1.11	28	350	0.19	23	100	142	
B290313		0.61	300	6	1.22	25	630	111	1.13	34	370	0.20	23	120	274	
B290314		0.72	311	8	1.31	21	620	75	0.82	26	394	0.22	28	130	169	
B290315		0.79	399	10	1.23	21	570	105	0.68	32	387	0.24	30	120	248	
B290316		0.67	372	8	1.22	20	550	119	0.88	44	381	0.22	26	120	284	
B290317		0.62	313	6	1.31	24	670	93	1.19	34	388	0.21	24	120	201	
B290318		0.65	388	8	1.20	29	650	172	1.28	51	372	0.22	26	160	461	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	K
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	%
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B290319		0.42	0.469	13.4	7.17	7110	370	2.8	17	2.24	3.8	15	65	143	3.94	3.73
B290320		0.42	0.243	9.5	6.74	3840	650	2.6	7	2.12	2.0	10	77	101	3.39	3.55
B290321		0.34	0.285	9.5	7.27	4140	770	2.8	15	2.26	2.2	11	61	105	3.29	3.83
B290322		0.24	0.274	8.4	7.28	4710	890	2.8	15	2.41	1.1	12	66	104	3.31	3.86
B290323		0.32	0.308	8.3	7.18	4700	980	2.8	17	2.44	1.2	12	56	111	3.32	3.81
B290324		0.46	0.303	9.9	6.77	4300	580	2.5	12	2.20	2.3	13	59	112	3.48	3.50
B290325		0.46	0.266	8.9	6.93	4240	710	2.6	7	2.30	1.8	12	65	104	3.52	3.50

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05048596

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290319		0.63	377	8	1.17	33	720	199	1.67	59	354	0.22	25	170	574	
B290320		0.62	396	10	1.04	27	640	129	0.98	42	326	0.22	26	130	318	
B290321		0.62	379	9	1.21	25	700	142	1.15	47	373	0.22	25	130	352	
B290322		0.63	314	7	1.27	29	700	87	1.18	40	376	0.21	25	110	184	
B290323		0.63	300	8	1.25	31	670	101	1.21	44	368	0.21	25	120	205	
B290324		0.65	385	8	1.00	28	630	165	1.17	58	322	0.21	25	130	343	
B290325		0.69	383	7	1.01	33	680	127	1.09	44	322	0.22	26	150	295	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D. 4-JUL-2005
Account: STRGOL

CERTIFICATE VA05049478

Project: 1735

P.O. No.:

This report is for 17 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 23-JUN-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05049478

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290326		1.04	<0.005	34.5	6.30	>10000	390	2.5	30	2.25	2.8	27	76	324	4.05	3.52
B290327		0.16	0.385	4.1	6.96	4870	1160	2.7	22	1.94	1.3	14	48	120	3.70	3.22
B290328		0.70	0.878	83.3	5.46	>10000	360	2.1	49	2.03	5.7	38	63	438	5.29	3.27
B290329		1.06	0.483	20.3	6.08	9610	690	2.4	19	2.15	2.3	20	84	166	3.40	3.29
B290330		0.32	0.641	5.9	6.23	7510	1010	2.2	6	2.39	1.9	18	64	91	3.84	2.98
B290331		0.52	0.523	4.2	6.34	5680	1380	2.4	5	2.39	2.0	13	56	83	3.38	3.35
B290332		0.36	0.684	14.6	6.35	8960	810	2.4	10	2.39	2.5	19	56	120	4.09	3.09
B290333		0.34	0.468	12.5	6.54	6050	1520	2.4	6	2.34	1.6	16	60	105	3.91	2.90
B290334		0.38	0.360	15.8	6.33	5030	1670	2.3	7	2.43	0.8	15	68	123	3.76	3.05
B290335		0.36	0.275	15.5	6.92	4240	1610	2.4	8	2.52	1.1	13	74	119	3.60	3.29
B290336		0.34	0.476	15.0	6.44	6240	1470	2.2	9	2.66	1.2	17	62	115	4.09	3.01
B290337		0.30	0.548	11.2	5.98	6880	1010	2.0	7	2.47	1.6	20	59	116	4.16	2.84
B290338		0.32	0.687	23.6	5.90	8860	710	2.0	9	2.58	1.6	24	54	265	4.60	2.62
B290339		0.34	0.877	27.7	5.99	>10000	300	2.0	17	2.64	2.1	30	63	241	5.06	2.69
B290340		0.44	0.836	31.2	5.89	>10000	300	2.1	12	3.24	1.3	36	56	273	5.78	2.45
B290341		0.50	0.755	24.4	5.59	9900	290	2.0	15	3.49	0.9	36	62	247	5.76	2.36
B290342		0.34	0.661	18.0	6.25	8730	800	2.2	7	2.93	1.1	26	63	183	4.98	2.75

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: 1735

CERTIFICATE OF ANALYSIS VA05049478

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B290326		0.54	380	4	1.03	46	730	201	2.19	95	313	0.18	20	400	446
B290327		0.81	866	10	0.78	29	720	541	0.54	225	249	0.30	48	70	242
B290328		0.45	441	6	0.86	75	680	359	3.13	146	274	0.17	17	980	854
B290329		0.51	332	4	1.01	39	670	160	1.75	67	304	0.17	19	260	334
B290330		0.76	385	8	0.93	34	920	164	1.24	54	313	0.21	29	110	270
B290331		0.68	371	7	0.96	25	740	149	1.09	43	313	0.20	26	80	309
B290332		0.73	384	12	0.88	36	820	213	1.56	62	308	0.19	25	170	341
B290333		0.88	400	24	0.74	35	810	142	1.15	41	299	0.22	32	140	258
B290334		0.94	428	44	0.72	38	750	114	1.06	38	292	0.22	37	170	212
B290335		0.91	433	31	0.88	37	790	78	1.01	29	320	0.22	35	170	192
B290336		0.93	458	35	0.74	41	950	109	1.28	33	297	0.21	34	160	216
B290337		0.91	474	26	0.59	44	930	131	1.37	29	265	0.20	33	140	296
B290338		0.98	511	15	0.54	49	1120	156	1.64	44	258	0.20	33	220	272
B290339		0.99	519	27	0.61	59	1020	178	1.98	50	266	0.20	33	290	321
B290340		1.39	591	12	0.53	69	1050	150	2.11	51	270	0.21	40	310	219
B290341		1.56	616	12	0.53	71	1140	134	1.89	38	274	0.20	42	200	175
B290342		1.25	532	14	0.64	53	870	128	1.64	36	286	0.22	40	200	210

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da[illegible]-JUL-2005
Account: STRGOL

CERTIFICATE VA05053955

Project: Dublin- Gulch-1735

P.O. No.:

This report is for 45 Stream Sediment samples submitted to our lab in Vancouver, BC, Canada on 4-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
SCR-41d	Screen to -100um, save both

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUL-2005
Account: STRGOL

Project: Dublin- Gulch-1735

CERTIFICATE OF ANALYSIS VA05053955

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290343		1.58	0.046	14.7	7.74	848	830	2.2	5	0.83	10.1	18	50	128	3.19	1.74
B290344		2.18	0.043	8.6	7.71	872	800	2.2	3	1.05	10.3	13	41	112	3.21	2.08
B290345		2.10	0.055	3.5	7.74	1535	1100	2.1	<2	1.40	2.1	12	39	88	2.84	3.12
B290346		1.22	0.047	13.2	7.61	1220	1160	2.3	2	1.86	1.6	13	34	109	2.74	2.58
B290347		2.82	0.039	4.8	7.63	1355	1300	2.3	<2	1.59	1.2	14	38	100	2.51	3.35
B290348		2.80	0.487	18.4	7.23	2740	910	2.4	45	1.53	1.8	17	42	229	3.21	2.84
B290349		0.74	0.325	41.6	7.68	1780	1030	2.8	39	2.00	2.4	19	92	276	3.70	3.36
B290350		1.78	0.482	5.4	7.34	2600	990	2.3	26	1.68	3.0	20	181	123	4.07	2.63
B290351		0.24	0.119	14.4	7.38	1395	680	2.4	10	1.90	3.6	7	134	121	3.20	1.96
B290352		1.82	0.110	4.1	6.51	1275	1320	2.2	7	2.15	3.7	7	200	126	3.06	2.05
B290353		0.78	0.172	56.8	7.15	2710	1540	2.6	15	1.60	2.5	15	253	352	5.62	3.28
B290354		1.08	0.304	44.1	7.22	2810	1540	2.8	28	1.78	0.9	17	121	291	4.25	3.87
B290355		0.46	0.284	39.6	7.11	1880	1260	2.8	35	2.31	1.2	12	82	262	3.27	4.06
B290356		0.20	0.064	>100	8.18	2050	1090	3.1	<2	0.33	1.1	15	94	305	3.88	3.75
B290357		0.28	0.070	>100	7.02	2320	1010	2.7	<2	0.35	<0.5	16	86	438	3.41	3.24
B290358		0.40	0.086	>100	6.93	2100	1000	2.7	<2	0.32	3.1	15	83	376	3.47	3.19
B290359		0.30	0.064	>100	8.07	2040	1190	3.2	<2	0.31	2.5	16	95	384	3.79	3.77
B290360		0.30	0.021	65.8	9.92	1180	1510	4.0	<2	0.25	0.7	14	100	195	3.74	4.28
B290361		0.36	0.047	>100	8.26	1660	1300	3.3	<2	0.26	<0.5	14	94	265	3.71	3.64
B290362		0.38	0.049	>100	7.73	1775	1040	3.1	<2	0.26	<0.5	14	86	341	3.47	3.49
B290363		0.40	0.071	>100	6.17	2440	790	2.3	<2	0.35	0.8	16	80	364	3.37	3.14
B290364		0.42	0.085	>100	6.56	2400	930	2.5	<2	0.38	<0.5	17	81	349	3.33	3.12
B290365		0.34	0.127	>100	6.32	2360	930	2.4	<2	0.35	0.6	17	97	375	3.93	3.07
B290366		0.32	0.093	>100	6.18	3010	790	2.3	<2	0.32	<0.5	19	75	439	3.37	2.86
B290367		0.28	0.064	>100	6.86	2160	810	2.6	<2	0.42	0.6	15	82	308	3.77	3.03
B290368		0.22	0.233	>100	6.38	2220	780	2.4	<2	0.33	1.2	14	94	394	4.20	3.12
B290369		0.22	0.039	53.4	7.03	1000	1220	2.2	<2	0.39	0.9	11	158	180	4.70	3.42
B290370		0.46	0.088	66.1	6.38	1405	1930	2.3	<2	0.34	<0.5	12	164	193	4.88	3.07
B290371		0.48	0.038	57.1	6.36	1105	1820	2.1	<2	0.36	<0.5	10	157	180	4.67	3.06
B290372		0.42	0.037	55.2	6.35	1215	1830	2.2	<2	0.34	<0.5	10	148	172	4.37	3.08
B290373		0.44	0.033	56.0	6.30	1395	1120	2.1	<2	0.33	1.2	11	118	185	4.05	3.01
B290374		0.20	0.037	54.0	7.26	1045	1580	2.3	<2	0.41	<0.5	12	171	171	5.06	3.40
B290375		0.50	0.152	88.8	7.00	1525	1570	2.5	<2	0.36	1.4	15	143	257	4.52	3.30
B290376		0.48	0.067	68.2	6.94	1460	1730	2.3	<2	0.37	<0.5	13	140	216	4.66	3.16
B290377		0.28	0.134	>100	5.75	1475	900	1.9	<2	0.45	<0.5	13	107	290	3.76	2.70
B290378		0.48	0.081	65.4	5.59	1315	1320	1.7	<2	0.41	1.1	14	124	192	3.99	2.67
B290379		0.22	0.097	59.5	6.07	1090	1120	1.8	<2	0.38	<0.5	12	134	203	4.44	2.99
B290380		0.38	0.089	49.0	6.41	1140	1700	2.1	<2	0.35	0.7	13	155	168	4.72	3.03
B290381		0.24	0.199	68.7	6.22	1410	1040	1.9	<2	0.39	0.8	14	140	220	4.61	2.99
B290382		0.24	0.342	91.7	6.19	1460	1340	1.9	<2	0.57	<0.5	15	147	289	5.04	2.88

Comments: SAMPLE B290387 UNABLE TO PROCESS DUE TO OILY SUBSTANCE. NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUL-2005
Account: STRGOL

Project: Dublin- Gulch-1735

CERTIFICATE OF ANALYSIS VA05053955

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290343		0.78	1440	19	0.53	140	450	394	0.24	45	103	0.15	19	320	1705	
B290344		0.67	1410	10	0.63	69	500	302	0.25	26	133	0.16	21	170	1740	
B290345		0.66	792	7	0.58	20	470	207	0.32	32	162	0.17	23	50	513	
B290346		0.64	1030	9	0.68	24	530	133	0.21	32	188	0.19	22	130	340	
B290347		0.59	730	5	0.41	20	510	106	0.18	29	156	0.21	26	70	295	
B290348		0.66	855	7	0.35	29	480	229	0.17	79	154	0.19	25	190	497	
B290349		0.52	999	21	0.35	55	590	298	0.14	112	134	0.24	31	540	644	
B290350		0.58	1030	29	0.47	48	500	304	0.23	106	177	0.19	25	170	573	
B290351		0.76	1070	24	0.63	20	470	650	0.20	174	148	0.18	20	200	384	
B290352		0.74	1080	27	0.47	42	450	412	0.34	119	151	0.17	20	140	376	
B290353		0.39	894	69	0.66	60	680	442	0.19	69	207	0.22	31	780	444	
B290354		0.38	513	30	0.88	67	750	77	0.12	55	235	0.27	35	870	262	
B290355		0.32	591	23	0.35	47	760	134	0.13	57	142	0.28	36	570	228	
B290356		0.71	214	12	0.79	61	390	26	0.10	10	144	0.26	72	800	91	105
B290357		0.60	192	9	0.74	73	320	27	0.15	14	136	0.22	59	1320	96	142
B290358		0.58	198	12	0.75	67	320	22	0.11	11	132	0.22	58	1100	81	136
B290359		0.70	196	11	0.84	72	340	25	0.10	13	146	0.25	73	1100	78	127
B290360		0.87	176	8	0.86	51	400	31	0.06	10	155	0.33	96	440	86	
B290361		0.67	196	11	0.68	56	330	27	0.05	9	136	0.27	75	720	73	110
B290362		0.63	186	10	0.68	66	320	25	0.06	5	129	0.24	67	890	72	103
B290363		0.56	206	12	0.80	65	310	19	0.12	12	137	0.19	46	1030	66	157
B290364		0.55	202	12	0.70	71	340	22	0.11	9	138	0.20	50	1020	65	156
B290365		0.58	241	15	0.75	70	340	25	0.11	20	132	0.20	50	1130	72	159
B290366		0.53	194	11	0.62	74	320	19	0.13	11	120	0.19	47	1340	68	185
B290367		0.69	231	11	0.74	62	330	17	0.09	12	135	0.23	56	890	73	107
B290368		0.59	258	17	0.85	79	340	20	0.09	30	128	0.20	50	1090	81	148
B290369		0.80	328	27	0.89	42	340	17	0.07	21	140	0.23	66	440	69	
B290370		0.63	330	29	0.80	45	320	21	0.11	19	134	0.21	57	470	71	
B290371		0.68	332	28	0.83	45	320	14	0.09	17	132	0.22	58	490	66	
B290372		0.64	294	25	0.86	40	340	15	0.10	24	136	0.22	57	420	65	
B290373		0.60	267	21	0.83	38	310	14	0.10	21	128	0.20	54	460	66	
B290374		0.83	360	30	0.86	40	350	16	0.08	18	140	0.25	68	430	69	
B290375		0.70	302	22	0.80	54	360	24	0.13	15	136	0.24	64	690	89	
B290376		0.69	318	24	0.80	47	340	20	0.13	20	134	0.22	59	550	76	
B290377		0.62	280	18	0.73	55	320	18	0.14	13	126	0.19	46	850	78	99
B290378		0.63	308	20	0.69	41	300	24	0.15	14	118	0.19	48	510	83	
B290379		0.69	334	23	0.74	42	330	23	0.13	18	120	0.19	53	530	90	
B290380		0.70	346	26	0.79	42	320	13	0.12	14	131	0.22	60	420	76	
B290381		0.69	349	25	0.75	47	330	16	0.14	14	122	0.20	54	570	84	
B290382		0.76	457	26	0.66	56	360	19	0.31	16	130	0.21	55	740	89	

Comments: SAMPLE B290387 UNABLE TO PROCESS DUE TO OILY SUBSTANCE. NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUL-2005
Account: STRGOL

Project: Dublin- Gulch-1735

CERTIFICATE OF ANALYSIS VA05053955

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	ME-ICP61 K % 0.01
B290383		0.28	0.664	70.8	4.59	1150	910	1.4	7	0.84	<0.5	17	132	281	4.91	1.92
B290384		0.26	0.678	64.7	3.78	1015	640	1.2	20	0.93	<0.5	17	133	277	4.71	1.48
B290385		0.28	1.000	78.2	4.32	1100	810	1.3	6	0.98	0.9	21	156	338	5.39	1.80
B290386		0.36	1.230	65.7	4.01	832	740	1.2	19	0.93	<0.5	16	125	277	4.63	1.50
B290387		0.38														

Comments: SAMPLE B290387 UNABLE TO PROCESS DUE TO OILY SUBSTANCE. NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUL-2005
Account: STRGOL

Project: Dublin- Gulch-1735

CERTIFICATE OF ANALYSIS VA05053955

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn	Ag
	Units	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2	1
B290383		0.77	569	26	0.37	54	380	14	0.49	12	113	0.19	47	570	87	
B290384		0.73	608	27	0.25	56	360	17	0.56	9	104	0.18	41	500	89	
B290385		0.82	662	31	0.29	64	370	14	0.68	12	116	0.18	46	640	95	
B290386		0.79	609	26	0.28	51	390	13	0.47	8	108	0.19	46	500	100	
B290387																


Comments: SAMPLE B290387 UNABLE TO PROCESS DUE TO OILY SUBSTANCE. NSS is non-sufficient sample.

APPENDIX E

Dublin Gulch 2005 Drill Sections

Costs associated with this report have been approved in the amount of $ 609.500 for assessment credit under Certificate of Work No. QM00527 & 611 QM00636 & 647

Mining Recorder
Mayo Mining District




Legend

094876

StrataGold Corporation

Date:25/10/2005	Dublin Gulch Section 458450 E (Hist Nad 27) DG05-292C and DG05-293C
Author: DH	
Office: Vancouver	
Drawing: 1	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres



Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999

Rock_Code_A Trace Shade
Rock_Code_A Text
LITH Trace Shade
LITH Text
Au_ppm Trace
Au_ppm Histogram Y manual at 1.2000
EOH

Legend for Au_ppm Legend for LITH

094876

StrataGold Corporation

Date:26/10/2005	**Dublin Gulch** **Drill Hole DG05-294C** **(459050 E, 7100740N)** **(Hist Nad 27)** **Looking SE at 120 deg.**
Author:	
Office: Vancouver	
Drawing: 2	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres

2100 mE
2200 mE
2300 mE
2400 mE
2500 mE
2600 mE
900 mN
800 mN
700 mN
DG05-284C
93-072R
DG05-282C
DG05-280C
DG05-288C
DG05-290C
TR459075E
MSED
QZZ
GND
GNDD

Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLB
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999


Legend for Au_ppm Legend for LITH

094876

StrataGold Corporation

Date:26/10/2005	**Dublin Gulch** **Section 459075 E (Hist Nad 27)** **DG05-280C, DG05-282C,** **DG05-284C, DG05-288C, DG05-290C** **with Historic Drill Holes**
Author: DH	
Office: Vancouver	
Drawing: 3	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres



094876

StrataGold Corporation

	Dublin Gulch **Section 459125E (Hist Nad 27)** **STEINER ZONE** **DG05-296C** **with Historic Drill Hole**
Date:26/10/2005	
Author:	
Office: Vancouver	
Drawing: 4	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30

metres

2025 mE
2075 mE
2125 mE
2175 mE
2225 mE
2275 mE
2325 mE
2375 mE

925 mN
875 mN
825 mN
775 mN
725 mN

DG05-286C

GND
QZZ
GND
GND
MSED
GND
MSED
GND
MSED
GND
GND
MSED
MSED

Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

Rock_Code_A Trace Shade

Rock_Code_A Text

LITH Trace Shade

LITH Text

Au_ppm Text

Au_ppm Histogram 1 mm/unit at 1:2000

EOH

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999

Legend for Au_ppm Legend for LITH

094876

StrataGold Corporation

Date:27/10/2005	Dublin Gulch Section 459175 E (Hist Nad 27) DG05-286C
Author:	
Office: Vancouver	
Drawing: 5	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres

1850 mE
1950 mE
2050 mE
2150 mE
2250 mE
2350 mE

950 mN
850 mN
750 mN
650 mN

96-269R
DG05-298C

MSED
GND
MSED
GND
MSED
GND
MSED
GND

Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

Legend for LITH

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999

Legend for Au_ppm

094876

094876

StrataGold Corporation

Date:28/10/2005	Dublin Gulch Section 459275 E (Hist Nad 27) DG05-298C with Historic Drill Hole
Author:	
Office: Vancouver	
Drawing: 6	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres


2075 mE
2125 mE
2175 mE
2225 mE
2275 mE
2325 mE
2375 mE
2425 mE

925 mN
875 mN
825 mN
775 mN
725 mN

DG05-291C

GND

Legend




094878

StrataGold Corporation

	Dublin Gulch Section 459475 E (Hist Nad 27) DG05-291C
Date:28/10/2005	
Author:	
Office: Vancouver	
Drawing: 7	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres



Legend

094870

StrataGold Corporation

Date:28/10/2005	**Dublin Gulch** **Section 459525 E** **(Hist Nad 27)** **DG05-289C and DG05-300C**
Author:	
Office: Vancouver	
Drawing: 8	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres

92-044R

DG05-297C

DG05-287C

QZZ

BQAH

QZZ
BQAH

MSED

GND

GND

2150 mE
2200 mE
2250 mE
2300 mE
2350 mE
2400 mE
2450 mE
2500 mE

975 mN
925 mN
875 mN
825 mN
775 mN

Legend

Legend for Au_ppm

Legend for LITH

094876

StrataGold Corporation

	Dublin Gulch Section 459575 E (Hist Nad 27) DG05-287C and DG05-297C with Historic Drill Hole
Date:28/10/2005	
Author:	
Office: Vancouver	
Drawing: 9	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres

2175 mE
2225 mE
2275 mE
2325 mE
2375 mE
2425 mE
2475 mE
2525 mE

1000 mN
950 mN
900 mN
850 mN
800 mN

92-021R

DG05-281C

QZZ
BQAH
QZZ
BQAH
MSED
QZZ
GND
GND

Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999

Legend for Au_ppm Legend for LITH

094876

StrataGold Corporation

Date:30/10/2005	Dublin Gulch Section 459600 E (Hist Nad 27) DG05-281C with Historic Drill Hole
Author:	
Office: Vancouver	
Drawing: 10	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30
metres

2000 mE
2100 mE
2200 mE
2300 mE
2400 mE
2500 mE

1000 mN
900 mN
800 mN
700 mN

DG05-299C

MSED

GND

GND

DG05-301C

92-062R

92-023R

GND

GND

Legend

BAH
BQAH
BQB
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

Rock_Code_A Trace Shade

Rock_Code_A Text

LITH Trace Shade

LITH Text

Au_ppm Trace

Au_ppm Text

Au_ppm Histogram 1 vertical at 1/2000

EOH

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999

Legend for Au_ppm.Legend for LITH

094876

StrataGold Corporation

Date:30/10/2005	**Dublin Gulch Section 459625 E (Hist Nad 27) DG05-299C and DG05-301C with Historic Drill Holes**
Author:	
Office: Vancouver	
Drawing: 11	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres

2000 mE
2100 mE
2200 mE
2300 mE
2400 mE
2500 mE
1100 mN
1000 mN
900 mN
800 mN
92-043R
96-161R
DG05-278C
DG05-279C
93-068R
93-069R
96-153C
DG05-283C
92-031R
96-267R
QZZ
BQAH
MSED
GND

Legend

BAH
BQAH
BQS
CHR
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ


Legend for Au_ppm
Legend for LITH

094876

StrataGold Corporation

Date:30/10/2005	**Dublin Gulch Section 459675 E (Hist Nad 27) DG05-278C, 279C and 283C with Historic Drill Holes**
Author:	
Office: Vancouver	
Drawing: 12	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres



Legend

BAH
BQAH
BQS
CHN
DIOR
FLCD
FZ
GND
GNDD
HFLS
MGD
MSED
PHYL
QMON
QTZ
QZZ
SZ

Legend for Au_ppm

0 - 0.2
0.2 - 0.5
0.5 - 0.75
0.75 - 1
1 - 1.5
1.5 - 2
2 - 3
3 - 5
5 - 999


Legend for LITH

094876

StrataGold Corporation

Date:30/10/2005	**Dublin Gulch** **Section 459725 E** **(Hist Nad 27)** **DG05-276C, 277C, 285C and 295C** **with Historic Drill Hole**
Author:	
Office: Vancouver	
Drawing: 13	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres



StrataGold Corporation

094878

	Dublin Gulch Section 459775 E (Hist Nad 27) DG05-309C with Historic Drill Holes
Date:30/10/2005	
Author:	
Office: Vancouver	
Drawing:	
Scale: 1:500	Projection: Non-Earth (meters)

0 7.5 15 30

metres

1950 mE
2050 mE
2150 mE
2250 mE
2350 mE
2450 mE
150 mN
050 mN
950 mN
850 mN

DG05-305C
MSED
GND
MSED
BQS
GND
BQS
95-132R
MSED
GND
MSED
GND
95-133R
96-157C
96-196C
96-197C
91-016C
96-165R
GND
92-059R
MSED
TR459875E
GND
SZ
GND
GND
BQS
BQAH
GND
GND
SZ
GND
GND
FZ
GND
GND
QMON
BQS
GND
QMON
BQAH
GND
GND
GND
GND
GND

Legend

- BAH
- BQAH
- BQS
- CHN
- DIOR
- FLCD
- FZ
- GND
- GNDD
- HFLS
- MGD
- MSED
- PHYL
- QMON
- QTZ
- QZZ
- SZ

Rock_Code_A Trace Shade
Rock_Code_A Text
LITH Trace Shade
LITH Text
Au_ppm Text
ESH

StrataGold Corporation

094876

Dublin Gulch
Section 459875 E
DG05-305C
and Historical Drill Hole

Date:25/10/2005	
Author: DH	
Office: Vancouver	
Drawing: 16	
Scale: 1:750	Projection: Non-Earth (meters)


0 12.5 25 5
metres

1975 mE 2025 mE 2075 mE 2125 mE 2175 mE 2225 mE 2275 mE 2325 mE 2375 mE 2425 mE 2475 mE 2525 mE 2575 mE

1200 mN 1150 mN 1100 mN 1050 mN 1000 mN 950 mN 900 mN 850 mN

96-167R
96-158C
96-166R
DG05-303C
DG05-306C
DG05-307C
96-206R
DG05-308C

MSED
BQS
FZ
BQS
GND
BQS
GND
GND
GND
GND
GND
GND
GND
GND
MSED



094876

StrataGold Corporation

Date:31/10/2005	**Dublin Gulch** **Section 459925 E** **(Hist Nad 27)** **DG05-303C, 306C, 307C and 308C** **with Historic Drill Holes**
Author:	
Office: Vancouver	
Drawing: 16	
Scale: 1:750	Projection: Non-Earth (meters)


0 12.5 25 50
metres

1950 mE 2000 mE 2050 mE 2100 mE 2150 mE 2200 mE 2250 mE 2300 mE 2350 mE 2400 mE 2450 mE 2500 mE

1250 mN 1200 mN 1150 mN 1100 mN 1050 mN 1000 mN 950 mN

96-160C 95-134R 96-202R 95-130R 96-191C 96-201R 95-129R DG05-302C 96-203R 96-204R DG05-304C 96-205R

QZZ BQS GND MSED SZ




094876

StrataGold Corporation

Date:31/10/2005	**Dublin Gulch Section 460025 E (Hist Nad 27) DG05-302C and DG05-304C with Historic Drill Holes**
Author:	
Office: Vancouver	
Drawing: 17	
Scale: 1:750	Projection: Non-Earth (meters)

0 12.5 25 50
metres

094876



APPENDIX F

Dublin Gulch 2005 Diamond Drill Logs

094876

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-276C

PROJECT: Dublin Gulch - 1735	GROUND ELEVATION: 1039m
	BEARING: 000 / DIP: -50°
DATE STARTED: 23-May-05 / DATE COMPLETED: 27-May-05	COORD SYSTEM: NAD 27: EASTING: 459744 NORTHING: 7099236
	COORD SYSTEM: NAD 83: EASTING: 459624 NORTHING: 7099420
LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead	NAD 27 (CORRECTED for historic grid): EASTING: 459714 NORTHING: 7099246
	SECTION LINE 459714E (historic grid)
CONTRACTOR: Britton Brothers	**SAMPLING DETAILS**
	Sample Sequence: B291001 to B291113
DRILLING DETAILS	Requisition #: MASP448STRGOL.05Q Date Shipped: 26-May-05
Hole Diameter: HQ	Lab Record #: VA05042605 Date Received: 1-June-05
Overburden: 12.19m	Sample Sequence: B2910114 to B291298
Deviation:	Requisition #: MASP448STRGOL.05Q Date Shipped: 2-June-05
Casing: 21.94m	Lab Record #: VA05045435 Date Received: 15-June-05
Core Size: HQ	
Cement (# Bags): 0	Duplicates: B291002, B291022, B291042, B291062, B291082, B291102, B291122, B291142, B291162, B291182, B291202, B291222, B291242, B291262, B291282
Plug Depth: N/A	Preparation Duplicate/ Check Assay: B291009, B291029, B291049, B291069, B291089, B291109, B291129, B291149, B291169, B291189, B291209, B291229, B291249, B291269, B291289
Notes: No plug necessary.	Standards: B291010(3C), B291030(3C), B291050(3C), B291070(3C), B291090(3C), B291110(2B), B291130(4D), B291150(4D), B291170(4D), B291190(3C), B291210(2B), B291230(4D), B291250(4D), B291270(5E), B291290(1A)
	Blanks: B291016, B291036, B291056, B291076, B291096, B291116, B291136, B291156, B291176, B291196, B291216, B291236, B291256, B291276, B291296

FROM	TO	LITHOLOGY
12.19m	258.0m	GND

FROM	TO	ALTERATION
45m	65m	ox, ser, chl, arg
87m	100m	ox, ser, chl, arg, cb
113m	135m	ox, ser, chl, arg, cb
230m	250m	ox, ser, chl, arg, cb

FROM	TO	MINERALIZATION (Veins)
105m	160m	pyrite, pyrrhotite, arsenopyrite, minor chalcopyrite
185m	258m	

SURVEYS:

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (Corr + 27)	AZ (Corr + 26)
50	333	50.8	000	359
100	332.5	51.2	359.5	358.5
200	332.9	51.3	359.9	358.9
260	334.9	50.4	001.9	000.9

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 1 of 22
DRILL HOLE #: DG05-276C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd. Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered. Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-12.19			Casing - no core recovery						
10	12.19-258.00	12.19	14.59	GND (Main interval). GND is limonite stained. Core is extremely broken to grav/sand. Recovery is poor. GND has pervasive limonite in fracs and appears partially decomposed. Mineralogical characteristics include: 40% qtz, 30% hornblende, 20% biotite, 10% limonite & qtz veins				1		
10		14.59	15.24	Fault gouge unit. Limonite pervasive within grey gouge/crumbly brecciated GND with visible qtz eyes. Possible hydrothermally altered GND. Preferable interpretation is hyd. altered GND, within physically decomposed core.	1	1		3		1
10		15.24	17.49	Broken GND (gravel size to sandy clay). Note: poor core recovery, extensive limonite	2		1			4
10		17.49	17.70	Clay gouge fault zone. Core contains extensive predominant clay with visible quartz eyes, pieces of gravel-sized GND, essentially decomposed GND (hydrothermally alt'd) as from 14.59-15.24m.	1	1		4		1
10		18.29	20.88	Extremely poor core recovery (~20%). Round, gravel-sized GND.						
10		20.88	21.34	Core coherency is of sugary gravel; limonite coated pieces. Minor sericite, no visible sulphides.						
10		21.34	25.58	Qtz vn @ 22.63m; 30 degrees to CA, tr aspy dissem, ~0.5cm thick. Trace dissem pyrite @ ~23.26m w/in the GND, no obvious vns in area.						
10		25.58	25.91	GND becomes extremely broken to gravel/sand sizes. Pieces of qtz vns visible; no sulphides or structure observable. Heavy limonite staining.	1			1		1
10		25.91	30.48	Core is becoming more competent. Avg frac angles are ranging from 30-40° to CA. Limonite staining abundant & pervasive on frac srfc's; Qtz vn @ ~26.0m @ 70° to CA. qtz was cloudy grey w/ no visible dissem sulphides.	1					
10		30.48	32.35	Qtz vn @ ~30.60m @ 70° to CA, no visible sulphides, milky translucent color. Qtz vn @ ~30.82m @ 70° to CA, translucent milky qtz.						
10		32.35	33.03	V.broken core due to hydrothermal alt'n. Sugary core w/ minor clay (10%), abundant limonite staining. Minor qtz pc's indicate minor vning.	1			1		
10		34.02	34.90	Same as above only more abundant gravel sized pc's and less qtz vn chips.						
10		35.15	35.50	Milky & clear qtz vn @ 35.21m parallel to CA. No visible sulphides inclusive. A microvnlet @ ~45° to CA x-cutting the vn contained a few dissem aspy.	1					
10		36.56	36.58	Qtz vn @ 40-45° to CA. proximally w/in 5-8cm dissem aspy is present.						
10		37.55	39.62	Alt'd section of GND, extensively fractured. Abundant limonite pervasive & on fracs. Gravel/sand/clay consistency. Qtz pebbles observed indicating vning.	1			1		
10		39.62	41.10	Milky qtz vn @ 41.10m w/ dissem aspy @ 40° to CA. Surrounding 10cm on either side of vn have endured sericite alt'n & have pervasive limonite staining.	1					
10		41.10	42.55	Core is broken but displays qtz vning, which appears to have aided in decomposition of GND. Minor visible sericite (1-2%), pervasive limonite & on fracs. Minor dissem aspy & minor vugging w/in qtz vn pc's.	1	1		1		

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other			From	To					
																					lim	B291001	12.19	13.72	0.013		VA05042605	1.53	
																						B291002	12.19	13.72	0.107	DUP	VA05042605	1.53	
																						B291003	13.72	15.24	0.521		VA05042605	1.52	
																						B291004	15.24	16.76	0.024		VA05042605	1.52	0.338
																						B291005	16.76	17.49	0.079		VA05042605	0.73	1.305
																						B291006	17.49	17.70	0.164		VA05042605	0.21	
																						B291007	17.70	18.29	0.009		VA05042605	0.59	
																						B291008	18.29	19.81	0.018		VA05042605	1.52	0.329
																						B291009	18.29	19.81	0.018	PD/CA	VA05042605	1.52	
																						B291010	STANDARD 3C		0.081	3C	VA05042605		
																						B291011	19.81	20.88	2.400		VA05042605	1.07	0.34
																						B291012	20.88	21.34	0.111		VA05042605	0.46	
1	1	0.5	0.5	30									0.1									B291013	21.34	22.86	0.133		VA05042605	1.52	1.06
																						B291014	22.86	24.38	0.089		VA05042605	1.52	0.579
																						B291015	24.38	25.91	0.059		VA05042605	1.53	0.628
																						B291016	BLANK		<0.005		VA05042605		
1	1	0.25	0.25	70																		B291017	25.91	27.43	0.019		VA05042605	1.52	0.214
																						B291018	27.43	28.96	0.056		VA05042605	1.53	
																						B291019	28.96	30.48	0.034		VA05042605	1.52	
2	1	1	2	70																		B291020	30.48	32.00	0.073		VA05042605	1.52	
																						B291021	32.00	32.35	0.060		VA05042605	0.35	
																						B291022	32.00	32.35	0.090	DUP	VA05042605	0.35	
																						B291023	32.35	33.03	0.074		VA05042605	0.68	
																						B291024	33.03	35.05	0.229		VA05042605	2.02	
1	1	1.0	1.0	45									0.1					1				B291025	35.05	36.58	0.049		VA05042605	1.53	
1	1	2.0	2.0	40	45								0.1					1											
1		2.0											0.1					1				B291026	36.58	37.55	0.106		VA05042605	0.97	
																						B291027	37.55	38.10	0.072		VA05042605	0.55	
																						B291028	38.10	39.62	0.121		VA05042605	1.52	0.36
																						B291029	38.10	39.62	0.130	PD/CA	VA05042605	1.52	
																						B291030	STANDARD 3C		0.089	3C	VA05042605		
1	1	0.5	0.5										0.1					1				B291031	39.62	41.16	0.400		VA05042605	1.54	0.294
																						B291032	41.16	42.65	0.265		VA05042605	1.49	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 3 of 22	
DRILL HOLE #: **DG05-276C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered

Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		42.80	44.20	Extremely broken GND w/ heavy limonite staining. Some minor qtz pc's indicating vns present but no other info obtainable. Core varies from gravel size to sand to clay (predom sandy gravel).	1			1		5
10		44.20	44.93	25% qtz, 30% k-sp, 10% hbl, 30% bt & 5% other, incl. sulphides. Hydrothermal alt'n across numerous 1mm weathered vns throughout section. Granular limonite covers fractured srfc's. 97% core recovery; core broken into blocks up to 10cm long.	4			1	2	
10		44.93	45.72	1-2mm pyrite grains present w/ intense hydrothermal alt'n; ox'd to siderite on frac srfc's.	3	1		1	2	
10		45.72	46.22	Minor hematite noted, subhedral grains oxidized to bright red. Tiny carb vns, calc & siderite angles indistinguishable as vns are pervasive. Core is gouge to chunks ~6cm in diam.	4			2	2	
10		46.22	47.92	GND varies in degree of breakage from gouge to 15cm solid chunks. Fracs more reg @ 20° angle.	3			2	1	
10		47.92	48.77	Material shows remnants of GND (qtz eyes, bt) but is predom. gouged. Biotite alt'd to v. hard, black mineral. Minor (10%) calcite in frac dominated by limonite.	4			3	2	
10		48.77	49.50	Broken core into ~5cm diam chunks avg, w/ little alt'n except from 49.0-49.2m - gouge zone.	1			3	1	
10		49.50	49.80	Qtz vn seen surrounded by ~10cm pervasively alt'd GND. Ser, aspy noted dissem w/in, as well as limonite. Weakened GND.	1	1			1	
10		49.80	50.29	Broken core. Gouge section 50.7-50.8m. Limonite on fracs, 1mm diam w/ minor calc.	2			1	1	
10		50.29	51.82	GND: broken core; 10cm avg length, reg frac @ 70°.	1				1	
10		51.82	53.34	GND core quite competent; broken along limonitic veinlets. Hematite staining noted in 1-3cm lengths. @ 52.17m: <1cm qtz vn alters GND (limonitic), as well at 53.1m. Aspy seen.	1	1	1		1	
10		53.34	54.86	GND. Pervasive limonite vning, random orient., competent core from 53.5-54.6m, rest is limonized & broken into 5cm blocks max.	1	1		1	1	
10		54.86	56.39	GND: small gouge section @ 55m, otherwise broken into ~5cm diam avg blocks w/ extensive 1mm vns of limonite. 2 qtz vns.	2	2		3	1	
10		56.39	57.91	Fewer mafics in GND where qtz is more smeared out (silicified zone). Aspy appears dissem @ 56.7m & 57.3m . These areas contain more competent core chunks up to 15cm long.	1		1	1		
10		57.91	58.80	Highly broken GND. Qtz vns (3) <2cm wide w/ no sulphides btwn 58.3-58.5m.	2	1		1	1	
10		58.80	59.44	Aspy appears in close proximity to qtz vn. 2 more qtz vns w/ dissem sulphides. Gouge @ 59.1m (adjacent to 2nd qtz vn).	2	1		2	1	
10		59.44	60.96	Competent section (low mafics) to 59.6m followed by limonite-pervasive gouge to fault breccia to 60.96m. Qtz found at 60.5m in centre of gouge material. No sulphides visible.	3	2		2	2	
10		60.96	62.48	Broken GND core. Qtz vns w/in most competent sections; no sulphides noted, no selvages.	2	1		2	2	
10		62.48	64.01	Extremely broken GND. Pc's 11cm long to gouge-sized particles. One thin (0.5cm) qtz vn at 62.5m w/ tiny alt'n ring.	3	2		3	2	
10		64.01	65.00	Gouge and remnant grains of GND to 64.5m. Rock is more competent @ 64.5m to 65.0m; blocks 10cm max.	4	3	2	2	2	
10		65.00	66.40	Pure qtz section to 65.3m. GND to 65.53m for 15cm, then GND to 66.4m. Dissem bt (1%) on frac faces. 5-sided rust print on one qtz sect (~4cm), no rxn rims visible.	1	1			1	
10		66.40	66.86	Angular gravel sized GND, some whole core.	1			1		5
10		66.86	68.02	Good recovery. 2cm qtz vn w/ dissem py & aspy. Near selvage, limonite stained frac perpendicular to vn.	1					5
10		68.02	68.58	Gouge contains remnant GND, qtz eyes, minor clay. Hydrothermal alt'n of GND.	2			1		4
10		68.58	69.98	Good recovery. White qtz vns at 65° & 35°. Minor dissem py & aspy, limonitic fracs.	1					5
10		69.98	70.46	Good recovery. <1cm qtz vns present. Minor dissem py & aspy.	1					5
10		70.46	71.24	White qtz vns at 40°, limonized fracs.	1					5
10		71.24	71.63	Broken GND, up to 10cm long. Limonized fracs, white qtz vn (1.5cm). Broken pc's qtz ~2cm, GND decomposed, hydrothermally alt'd.	2	1		2		3
10		71.63	72.92	Gravel-sized GND, rounded. Some clay present, qtz eyes, white qtz vn.	1					

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages														Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B291033	42.65	44.20	0.101		VA05042605	1.55	
																						B291034	44.20	44.93	0.114		VA05042605	0.73	
1	1	1.0	1.0	80		0		0		2.0								2				B291035	44.93	45.72	0.069		VA05042605	0.79	
																						B291036	BLANK		<0.005		VA05042605		
	4	0.1	0.1															0				B291037	45.72	46.22	0.057		VA05042605	0.50	
2	1	1.0	2.0	10		0		0										0				B291038	46.22	47.92	0.073		VA05042605	1.70	
																						B291039	47.92	48.77	0.416		VA05042605	0.85	
																						B291040	48.77	49.50	0.058		VA05042605	0.73	
1	1	1.0	1.0	90		10		2		2.0			2.0					1				B291041	49.50	49.80	0.895		VA05042605	0.30	
1	1	1.0	1.0	90		10		2		2.0			2.0					1				B291042	49.50	49.80	0.222	DUP	VA05042605	0.30	
																						B291043	49.80	50.29	0.027		VA05042605	0.49	
3	1	1.0	3.0	45		1		2		0.0								0			s&cb	B291044	50.29	51.82	0.353		VA05042605	1.53	
2	1	0.5	1.0	80		2	s/cb	2		1.0			2.0									B291045	51.82	53.34	0.170		VA05042605	1.52	0.36
																						B291046	53.34	54.86	0.142		VA05042605	1.52	
2	1	0.5	1.0	50		2		2														B291047	54.86	56.39	0.191		VA05042605	1.53	
																						B291048	56.39	57.91	0.106		VA05042605	1.52	0.294
																						B291049	56.39	57.91	0.094	PD/CA	VA05042605	1.52	
																						B291050	STANDARD 3C		0.090	3C	VA05042605		
3	1	0.5	1.5	40		0		0		0.0												B291051	57.91	58.80	0.103		VA05042605	0.89	
3	1	1.0	3.0	70		2	cb/s	4					3.0									B291052	58.80	59.44	0.058		VA05042605	0.64	
1	1	1.0	1.0	60																		B291053	59.44	60.96	0.043		VA05042605	1.52	
3	1	0.5	1.5	50		0																B291054	60.96	62.48	5.580		VA05042605	1.52	
1	1	0.5	0.5	80		0																B291055	62.48	64.01	0.279		VA05042605	1.53	
																						B291056	BLANK		<0.005		VA05042605		
1	1	1.0	1.0	50		0																B291057	64.01	65.00	0.222		VA05042605	0.99	
2	1	10.0	15.0	60		0				0.0												B291058	65.00	66.40	0.025		VA05042605	1.40	
																						B291059	66.40	67.07	0.114		VA05042605	0.67	
2	1	2.0	3.0	55					1	2.0			1.0								lim	B291060	67.07	67.31	1.805		VA05042605	0.24	
																						B291061	67.31	68.02	0.196		VA05042605	0.71	
																						B291062	67.31	68.02	0.189	DUP	VA05042605	0.71	
																						B291063	68.02	68.58	0.698		VA05042605	0.56	
5	1	1.0	5.0	65	35				1	1.0											lim	B291064	68.58	69.98	0.089		VA05042605	1.40	
4	1	0.5	2.0	65	35				0	1.0			1.0									B291065	69.98	70.46	0.016		VA05042605	0.48	
3	1	1.5	4.0	40		0.5																B291066	70.46	71.24	0.148		VA05042605	0.78	
1	1	1.5	1.5																		lim	B291067	71.24	71.63	0.049		VA05042605	0.39	
1	1	1.0	1.0																			B291068	71.63	72.92	0.077		VA05042605	1.29	
1	1	1.0	1.0																			B291069	71.63	72.92	0.071	PD/CA	VA05042605	1.29	
																						B291070	STANDARD 3C		0.809	3C	VA05042605		

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized, 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered
Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From	To:		ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		72.92	73.15	Qtz vns at top, in competent core, changes to gougy GND; hydrothermal alt'n related to qtz vning.	1			1		
10		73.15	74.02	Gravel-sized GND & qtz, rounded, limonized.	1					
10		74.02	74.49	Gouge, partially alt'd GND, clays w/ qtz eyes & gravel-sized GND, hydrothermal alt'n, limonitic.	2	1		2		
10		74.49	78.12	Broken core, limonized fracs. Qtz vn @ 45°, 8cm qtz lens at 77.72m, minor aspy in some vns.	1	1				
10		78.12	79.08	Good recovery. GND w/ qtz vns at 30°, minor aspy. Fracs show limonite. Py and strong sulphur smell present.						
10		79.08	80.37	GND w/ qtz vns at 30°, fracs are limonitic, dissem aspy btwn 80.19-80.37m, highly oxidized.	2					
10		80.37	80.70	2 massive sulphide vns ~3cm, aspy & scorodite & py present, GND highly alt'd, vuggy.	2					
10		80.70	82.30	Small qtz vns <1cm, limonized frac. Alt'd at 82.0-82.10m, gravel-sized GND w/ clay--hydrothermal.	2	1			1	
10		82.30	83.82	Good recovery. Limonized fracs, 7 qtz vns ~1cm thick, in conjugate sets, 2 series of vn emplacement. Gouge at 83.72-83.82m, qtz eyes present w/ remnant GND w/ hydrothermal alt'n.	1				1	
10		83.82	85.34	<1cm qtz vns in GND, limonized fracs alter rock from 83.22-83.42m. Qtz eyes & hydrothermally alt'd GND present. Preceded & followed by qtz vns at 45°.						
10		85.34	86.87	Good recovery. Limonized fracs, qtz vns <1cm, dissem aspy.	1	1		1		
10		86.87	87.35	Good recovery. Limonized fracs, 2 series of vn emplacement, 1st qtz at 45°, 2nd qtz & calc at 30°, minor aspy present in margins of both vns.	1					
10		87.35	87.93	Highly oxidized GND containing qtz & calc vns. Alt'd to clay w/ GND frags & qtz eyes from 87.65-87.75m. Hydrothermal continues after as oxidation w/ vns. Aspy present in qtz vn margin.	4	2				
10		87.93	88.39	Slightly oxidized GND hosting several small qtz vns. Vns are oxidized at margins. Aspy present in margins.	1					
10		88.39	89.38	Gravel-sized GND mixed w/ clay shows more intense alt'n after 88.8m; higher clay content & becoming crumbly. Qtz eyes present in the clay; possible fault or hydrothermal alt'n. Remnant GND in clay indicates hydrothermal more likely. Gravel size pc's of qtz, possible vns weathered.	2	1		2		
10		89.38	90.74	Slightly alt'd GND w/ limonized fracs grades to gravel sized GND btwn 89.92-90.06m. Qtz vns <1cm present, minor aspy in rim.	1	1		1		
10		90.74	90.99	Alt'd & oxidized GND. Brownish red in color, alt'd to sericite & clays. Qtz eyes present--hydrothermal.	3	1		2		
10		90.99	91.24	Highly oxidized & alt'd GND. Zone of intense clay alt'n; fault gouge at 91.09m, qtz vn <1cm.	3	2		3		
10		91.24	92.11	Mod ox'n & alt'n. Brownish red color. Mushy texture w/ qtz eyes & pebble sized GND; hydrothermal alt'n.	3	1		2		
10		92.11	92.96	Less ox'd & alt'd. Milky qtz vns <1cm. Small zones (1-2cm) of intense alt'n above & below vns. Qtz eyes present in zones; likely hydrothermal. Milky white qtz vns at 92.44m @ indeterminate angle w/ trace aspy at margin. Vn @ 92.70m: 0.5cm, grey, @ indeterminate angle due to alt'n, tr. aspy at margin.	2	1		1		
10		92.96	93.97	High alt'n btwn 92.96-93.14m. Mod alt'n (1) until 93.79-93.90m, which shows high alt'n to clays. Qtz vns at 70° to CA at 93.11m, 1cm diam. Vn @ 93.14m: 3.5cm @ 65° to CA, grey.	2	1		1		
10		93.97	94.49	Mod alt'n (2) until 94.03m where alt'n becomes higher (3). Qtz eyes present throughout clays & GND, likely hydrothermal alt'n. Minor sericite present.	2	1		2		
10		94.49	95.48	Slightly alt'd (1) but mod ox'n in GND. Highly alt'd (4) at 94.90-94.95m & at 95.32-95.38m to clay w/ qtz eyes & GND frags. Broken qtz vn @ 95.4m, grey.	3	1				
10		95.48	96.51	Good recovery. Mod ox'n in GND w/ limonitic fracs. Sericite in fracs & alt'n halos. Qtz vns @ 96.23m, ox'd vn w/ 3% ox'd py & 1% ox'd aspy in vn margin & halo.	2	1				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.5	2.5	65																		B291071	72.12	73.15	0.533		VA05042605	1.03	
																						B291072	73.15	74.02	0.235		VA05042605	0.87	
																						B291073	74.02	74.49	0.233		VA05042605	0.47	
2	1	1.5	2.5	45																		B291074	74.49	75.29	0.104		VA05042605	0.80	
5	1	2.0	7.0	45																		B291075	75.29	75.71	0.126		VA05042605	0.42	
																						B291076	BLANK		<0.005		VA05042605		
5	1	1.2	4.0	45																		B291077	75.71	76.76	0.154		VA05042605	1.05	
3	1	1.0	3.0	45																		B291078	76.76	78.12	0.356		VA05042605	1.36	
3	1	1.5	4.0	30		7	s	3	2	5.0					10						lim	B291079	78.12	79.08	9.990		VA05042605	0.96	
5	1	0.5	2.5	30																		B291080	79.08	79.40	0.692		VA05042605	0.32	
3	1	2.0	4.0	45																		B291081	79.40	79.90	0.682		VA05042605	0.50	
3	1	2.0	4.0	45					1				1.0								lim	B291082	79.40	79.90	0.443	DUP	VA05042605	0.50	
3	1	1.0	1.5	45														4				B291083	79.90	80.37	0.601		VA05042605	0.47	
2	6	3.0	5.0	40					2	5.0			25.0						4			B291084	80.37	80.70	2.530		VA05042605	0.33	
8	1	0.5	4.0	35																		B291085	80.70	82.30	0.348		VA05042605	1.60	
7	1	1.0	6.5	45	50								0.1					2				B291086	82.30	83.82	0.757		VA05042605	1.52	
6	1	1.0	4.5	45														2				B291087	83.82	85.34	0.230		VA05042605	1.52	
4	1	1.5	3.5	35		2	q	2	2				1.0									B291088	85.34	86.87	0.135		VA05042605	1.53	
4	1	1.5	3.5	35		2	q	2	2				1.0									B291089	85.34	86.87	0.187	PD/CA	VA05042605	1.53	
																						B291090	STANDARD 3C		0.090	3C	VA05042605		
4	1	1.0	2.0										1.0					1				B291091	86.87	87.35	0.468		VA05042605	0.48	
	3	0.2	2.0			2	q	3	3				1.0					1											
6	1	1.5	4.0	55		1	s	4	2				1.0					1				B291092	87.35	87.93	0.837		VA05042605	0.58	
	3	0.2	0.4																										
4	1	1.0	1.6	25									1.0									B291093	87.93	88.39	0.180		VA05042605	0.46	
																						B291094	88.39	89.38	0.190		VA05042605	0.99	
2	1	0.9	0.9										0.1									B291095	89.38	90.74	0.242		VA05042605	1.36	
																						B291096	BLANK		0.065		VA05042605		
																						B291097	90.74	90.99	9.530		VA05042605	0.25	
1	1	0.9	0.9																			B291098	90.99	91.24	0.657		VA05042605	0.25	
0																						B291099	91.24	92.11	0.261		VA05042605	0.87	
2	1	1.0	1.5										0.1									B291100	92.11	92.96	0.412		VA05042605	0.85	
2	1	3.5	4.5																			B291101	92.96	93.97	0.240		VA05042605	1.01	
																						B291102	92.96	93.97	0.125	DUP	VA05042605	1.01	
																						B291103	93.97	94.49	0.073		VA05042605	0.52	
1																						B291104	94.49	95.48	0.105		VA05042605	0.99	
1	1	0.2	0.2	30						3.0			1.0									B291105	95.48	96.51	0.162		VA05042605	1.03	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 7 of 22	
DRILL HOLE #: **DG05-276C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered

Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		96.51	97.54	Good recovery. Mod alt'd (2) & ox'd (2). Fracs show minor limonite. White qtz vns @ 96.84m, 1cm diam, contain 3% po in vns.	2	1				
				White qtz vn @ 97.14m, ox'd rim, 1cm, 35° to CA, 3% py in vns, ox'd py.						
10		97.54	98.10	Slightly alt'd GND. Less limonitic, minor in fracs. Vn @ 97.87m; 1cm milky white qtz @ 40° to CA contains cpy 1%, po 1%, aspy 3%, tr. magnetite. Microfault cuts vn.						
10		98.10	99.06	Good recovery. Minor ox'n from 98.92-99.06m. Fracs slightly limonitic. Grey qtz vn @ 98.85m @ 40°to CA. Grey qtz vn @ 98.9m; 0.5cm, ox'd margin.	1					
10		99.06	99.76	Mod alt'n (2-3) to sericite & clay. Qtz eyes & vns present, but are fractured & displaced. Hydrothermal or shear zone alt'n occurs at 45° to CA. White qtz vn @ 99.50-99.55m @ 60° to CA, tr py (ox) & aspy. Grey qtz vn @ 99.68m, 1cm, frac & displaced, 40° to CA.	1	2		2		
10		99.76	100.58	Start of good core. Weak limonite staining on fracs. Slightly alt'd, minor sericite in fracs. Vn @ 100.23m, 1cm at 40° to CA. no visible sulphides.	1	1		1		
10		100.58	102.11	Less ox'n than above. Vn @ 100.83m, 1cm at 40°, aspy in margin. Milky white qtz vns @ 101.15m, 101.19m, 101.33m, 1cm, tr aspy in margins @ 35°.	1			1		
10		102.11	103.63	Slightly altered GND - minor limonite on fracs. Vein @ 103.44: white qtz	1					
10		103.63	105.16	Slightly oxidized GND. V. little limonite in fracs. Veins run near parallel to CA w/ ox'd margins; py & aspy in margins						
10		105.16	106.68	Relatively unaltered GND. Limonite in fracs. Veins run parallel to CA. Aspy & py in margins. Py slightly oxidized						
10		106.68	108.20	Unaltered GND w/ minor limonite in fracs. Vein at 106.68-106.86m, 0.1cm, ox'd, white qtz at 45° to CA . Vn @ 106.90m: 1cm, grey, @40° to CA, 5% ox'd po, 1% ox'd py. Vein at 107.95m. 0.1cm white qtz with carbonate, at 70°, trace aspy.	1					
10		108.20	109.73	Core is fractured. Lim on few surfaces, qtz & carb veinlets					1	
10		109.73	110.34	Unaltered GND. Minor limonite on fractures. Vn @ 109.77: 0.5cm, at 50°, trace aspy, milky white qtz, offset by micro-fault. Veins at 109.97m and 110.19m, milky white qtz, at 40° to CA, minor po and trace cpy in veins.						
10		110.34	111.25	Unaltered GND. Minor limonite on fractures.						
10		111.25	112.05	Good recovery. Minor ox'n. Stain in fracs. GND is lightly bleached. Dissem po (5%) & aspy (tr.) & py (1%) through entire length.						
10		112.05	113.66	~30% ser alt'n around narrow veins. 13 veins noted. Angles are complimentary (45° & 145°)	1	3	1		1	
10		113.66	114.60	Section is entirely altered w/ sericite + ox'n w/ lim covering fracture planes	3	3	2	1		
10		114.30	115.09	GND same as above unit, but veins/fractures more randomly oriented (20-90°)	3	3	2	1		
10		115.09	116.05	1mm carb/ser. Veins fractured at reg angle: 125°/65°; these tiny veins overprint larger qtz veins w/ sulphides at 145°/35°	1	2	1		1	
10		116.05	116.80	4 qtz. vns. Have clear centres(1cm, max) w/ margins of milky qtz (1cm thick). Py & aspy are in granular clumps on margins and w/l clear qtz centres. Ser/qtz/carb veins: <1mm thick, ox'd. More frequent w/ fractures	1	1	2		1	
10		116.80	117.80	Zone of high alteration but rock is still coherent, except at 117.25 where clay alteration is ~5cm thick. Med. grade, low-angle fracturing has slickensides shown in sericite, perpendicular to breaking plane's long axis. Sulphides appear at margins of fault breccia section (117.05 - 117.13m). Massive sulphides w/ aspy @ exterior edges. py clumped into masses >8cm long and 1cm wide. At 117.5m, v. high chlorite alt'n; only indistinct qtz. grains left. Some are in lines, denoting overprinted veins between 117.45 to 117.80m. Trace po located w/in these lines.	1	3	3	1	1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
2	1	1.0	2.0	35						3.0	3											B291106	96.51	97.54	0.197		VA05042605	1.03	
2	1	1.0	1.5	40							1	1.0	3.0									B291107	97.54	98.10	4.000		VA05042605	0.56	
2	1	0.5	1.0	40																		B291108	98.10	99.06	0.064		VA05042605	0.96	
2	1	0.5	1.0	40																		B291109	98.10	99.06	0.068	PD/CA	VA05042605	0.96	
																						B291110	STANDARD 2B		3.180	2B	VA05042605		
2	1	1.0	2.0	40						0.1			0.1									B291111	99.06	99.76	0.470		VA05042605	0.70	
1	1	1.0	1.0	40																		B291112	99.76	100.58	0.767		VA05042605	0.82	
4	1	1.0	4.0	40	35								0.1									B291113	100.58	102.11	0.831		VA05042605	1.53	
1	1	1.0	1.0	40																		B291114	102.11	103.63	0.035		VA05045435	1.52	
1	1	1.0	1.0	85					2				0.1									B291115	103.63	105.16	0.131		VA05045435	1.53	
											-											B291116	BLANK		<0.005		VA05045435		
1	1	0.1	0.1	85		2	q	3	1	1.0			0.1									B291117	105.16	106.68	0.022		VA05045435	1.52	
3	2	1.0	1.1			2	q	2	2	1.0	5											B291118	106.68	108.20	0.036		VA05045435	1.52	
	3	0.1	0.1										0.1														VA05045435		
2	1	1.5	2.5	35	40				1	1.0			3.0					3				B291119	108.20	109.73	0.159		VA05045435	1.53	
3	1	1.0	2.7	50		1	q	2	1		1	0.1	0.1									B291120	109.73	110.34	0.035		VA05045435	0.61	
3	1	1.0	3.0	45							10											B291121	110.34	111.25	0.466		VA05045435	0.91	
3	1	1.0	3.0	45							10											B291122	110.34	111.25	0.477	DUP	VA05045435	0.91	
1	1	1.0	1.0	50							0.1											B291123	111.25	112.05	0.313		VA05045435	0.80	
10	4	0.2	2.0	45	145	6	s/cb	2	3	2.0												B291124	112.05	113.66	0.090		VA05045435	1.61	
3	3	1.0	3.0	45	135	1	q/chl	1	0	4.0			5.0																
2	3	1.5	2.0	30		2	chl/s/cb	3	3	1.0												B291125	113.66	114.30	0.470		VA05045435	0.64	
8	3	1.0	4.5			2	chl/s/cb	3	3	1.0												B291126	114.30	115.09	0.041		VA05045435	0.79	
3	1	3.0	8.0	145	35	4	chl/s/cb	2	2													B291127	115.09	116.05	0.192		VA05045435	0.96	
2	3	0.2	0.5	65	125					2.0			2.0																
3	1	4.0	7.0	25	45					0.1			2.0									B291128	116.05	116.80	0.237		VA05045435	0.75	
3	1	4.0	7.0	25	45					0.1			2.0									B291129	116.05	116.80	0.294	PD/CA	VA05045435	0.75	
																						B291130	STANDARD 4D		0.479	4D	VA05045435		
3	1	3.0	5.0	40		10	chl/s	3	0.5	8.0	0.1	0.1	2.0									B291131	116.80	117.80	0.256		VA05045435	1.00	
1	6	1.0	1.0	40	50																								

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 9 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.80	118.24	Relatively unaltered. Pervasive lens of sericite appears associated w/ qtz lens. Small, partially ox'd carb veins overprinting ser & qtz.	1	2	1	1	1	
10		118.24	118.97	Altered around 3 qtz veins.	0	2	1	1	1	
10		118.97	119.40	Angle at which altered zone turns to unaltered GND is 45°. Sample is unaltered GND. Lenses of po < 4cm long & 0.3cm wide seen adjacent to qtz vein at 119.30m						
10		119.40	119.59	2cm wide milky qtz vn has po & py concentrated in 0.5cm wide section in centre						
10		119.59	121.10	2cm^2 section of po (uneven cluster). @119.90m, a section of randomly-oriented veinlets of calcite plus one 0.5cm vein of massive sulphides (po, py & cpy) rimmed w/ calcite, to 30°. Qtz vein at 120.11m to 140° not much alt'n assoc. Rest of section relatively unalt'd GND. Qtz veins: @120.16m, 120.47m, 120.76m, 120.86m, 121.02m & 121.20m. All @45-50° to CA. These veins have inner sections of clear qtz, a few mm thick, and outer sections of milky qtz. Po and py seen inside clear qtz.						
10		121.10	122.20	Six qtz veins noted, to 121.43m, after which, there is a zone of highly alt'd (chl+ser) GND. Bleached zone at 121.5m, at 55° to CA, with 0.5cm qtz vein in centre. Qtz vein also at 55°, at 121.6m begins chl alt'n zone to 121.85m. 3cm sericite zone btwn 2 qtz veins 1cm thick; alt'd zone to 122.2m.		1	1		1	
10		122.20	123.50	Silicified sections 3cm wide w/ 3cm alteration halos at 122.27m, 122.4m, 122.63m & 123.2m. Orientation is always 45°. 1-2% py & po w/in bleached sections. 3 qtz veins @ 122.5m, 122.9m and 123.4m @50° to CA.						
10		123.50	125.00	GND w/ altered/bleached sections: 123.65-123.90m (gouge, last 4cm); 124.10-124.14m; 124.50-124.53m; 124.64-124.68m; 124.78-124.83m. Two of these sections have small qtz veins at centre.	0	3	2	2	1	
10		125.00	125.90	GND w/ altered sections: 125.65-125.66m; 125.79-125.80m; 126.40-126.60m.	0	3	1	1	1	
10		125.90	127.39	Sericitized & chloritized GND assoc. w/ 10 1-2cm qtz vns w/ sulphides. Vn locations: 125.9m (70°), 126.17m (60°), 126.23m (40°), 126.4m (70°), 126.44m (70°), 126.64m (70°), 126.74m (50°), 126.90m (40°), 127.26m (50°), & 127.35m (40°). Aspy concentrated @ margins of veins, py w/in vein and at margins	0	3	3	0	1	
10		127.39	128.66	Continued zone of alteration except from 127.39 → 127.5 where veins are <1mm and selvages <2cm Larger qtz veins w/ sulphides @ 127.88, 128.16, 128.21, 128.44 & 128.63m; sulphides situated similar to above.	0	3	3	1	1	
10		128.66	129.64	Sericite & chlorite GND. Qtz veins: @128.89m (60°); @129.42m (60°), trace aspy; @129.95m (90°), trace po; @129.45m (40°).						
10		129.64	131.10	Qtz veins contain trace po & as, lots of py, located: @129.89m (70°), @130.50m (70°), @130.68m (65°). Massive sulphide lens at 129.8-129.85m, 3cm wide. Tr po, py, aspy. Section is mostly s/chl alt'd w/ <10cm wide unalt'd sections.		3	3	1	1	
10		131.10	132.04	Qtz vein at 131.15m at low angle and contains no sulphides. Others, at high angle, contain po. Veinlet network of carbs surrounded by selvages of silicified GND (bleached)					1	
10		132.04	134.23	Unaltered GND w/ carb veinlets randomly oriented w/in. Bleached sections @132.34m (70°), 4cm wide; @132.84m (45°), 12cm wide; and @132.92m (45°), 2cm wide. These may be silicified veins; aspy and py in moderate amounts. Late calcite veinlets offset qtz vein offshoots to 20°. Qtz veins: @133.80m, to 35°, 3.5cm thick; @134.0m, to 35°, 0.3cm thick; and @134.08m, 35°, 1cm thick.		2	1			
10		134.23	134.70	Unaltered GND. Silicified qtz vein at 134.35m, to 45° w/ no sulphides. Vn at 134.52m, 60°, w/ assc po. Qtz/carb vein at 134.62m, at 45° to CA, w/ high percentage of po.		1				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	45		0.5	s/chl	2	0	2.0	2		0.1									B291132	117.80	118.24	0.037		VA05045435	0.44	
3	1	1.0	3.0			4	chl/q/s	2														B291133	118.24	118.97	0.082		VA05045435	0.73	
1	1	1.0	1.0	45		0.5	chl/q	1			2											B291134	118.97	119.40	0.062		VA05045435	0.43	
1	1	3.0	3.0	80		4	q/chl			1.0	5											B291135	119.40	119.59	0.125		VA05045435	0.19	
																						B291136	BLANK		<0.005		VA05045435		
1	1	1.0	1.0	140		1.5				1.0												B291137	119.59	121.10	0.926		VA05045435	1.51	
11	1	1.5	7.5	45		1	s/chl	1		0.1			0.1									B291138	121.10	122.20	0.716		VA05045435	1.10	
3	1	1.5	3.0	50		1	s/chl	1		2.0												B291139	122.20	123.50	0.413		VA05045435	1.30	
3	1	3.0	9.0	45		4				2.0	2																		
2	1	0.5	1.0	45		1	s/chl	2														B291140	123.50	125.00	0.972		VA05045435	1.50	
1	1	0.5	0.5	50		1	s/chl	1					3.0									B291141	125.00	125.90	0.049		VA05045435	0.90	
1	1	0.5	0.5	50		1	s/chl	1					3.0									B291142	125.00	125.90	0.062	DUP	VA05045435	0.90	
10	1	2.0	9.0	70	45	10	s/chl	4		4.0			3.0									B291143	125.90	127.39	0.165		VA05045435	1.49	
5	1	1.5	4.0	55	25	10	s/chl	4		4.0			2.0									B291144	127.39	128.66	0.492		VA05045435	1.27	
3	1	1.0	3.0	60	40	10	s/chl	5					0.1									B291145	128.66	129.64	1.195		VA05045435	0.98	
1	1	1.0	1.0	90		5	s/chl	5			0.1																		
3	1	2.0	4.0	70	65	0.5	s/chl	4		10.0	0.1		0.1									B291146	129.64	131.10	3.280		VA05045435	1.46	
1	6	3.0	3.0			10	s/chl	5		0.1	0.1		0.1																
1	1	1.0	1.0	55		0.5	s	1			10											B291147	131.10	132.40	0.478		VA05045435	1.30	
1	1	1.0	1.0	15		0.5	s	1																					
2	4	0.2	0.4	25	35	1	cb/q	2	1													B291148	132.04	133.22	0.628		VA05045435	1.18	
						12	cb/q	3		3.0			2.0														VA05045435		
2	4	0.2	0.4	25	35	1	cb/q	2	1													B291149	132.04	133.22	0.621	PD/CA	VA05045435	1.18	
						12	cb/q	3		3.0			2.0																
																						B291150	STANDARD 4D		0.475	4D	VA05045435		
3	1	3.5	7.0	35		10	s/chl	4	1	2.0	1		1.0									B291151	133.22	134.23	0.425		VA05045435	1.01	
1	1	2.0	3.0	50	20		s/chl				0.1																		
1	1	1.0	1.0	45		1	s/chl	1			0.0											B291152	134.23	134.70	0.288		VA05045435	0.47	
1	1	1.0	1.0	45		1	q	1			20.0																		
1	1	0.6	0.6	60		1	q	1			5.0																		

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 11 of 22	
DRILL HOLE #: DG05-276C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From	To:		ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		134.70	135.64	At 134.70m, turns to alt'd at an angle of 40°. Qtz veins: @135.01m (50°); @135.22m (25°); @135.27 (50°) - intersects with previous, same generation; @135.54 (45°). At 135.34m, alt'd turns to unalt'd at a 40° angle.	1	4	3	2	2	
10		135.64	137.16	Unaltered GND except from 136.18→136.26m where chl zone surrounds 0.5cm qtz vein at 50°, and from 136.59 to 137.12m around 1cm qtz vein at 70° to CA. Also in this interval at similar angles are veinlets of 'pure' sulphides surrounded by bleached sections, 2cm wide, within alt zone			1			
10		137.16	137.59	GND has multiple 1-2cm thick qtz veins @ an average angle of 40-60° to C.A., ~1-2% dissem py and aspy present within milky white qtz veins. Core is devoid of limonite staining. GND is still of consistent mineralogical nature, however, episodes of bleaching/leaching of minerals out have reduced sections to extremely sericitic/bleached and occasionally silicified veins @ 137.20m (@ 50°), 137.34 (@40°), w/ dissem py, po, aspy. Sericite on margins						
10		137.59	140.03	GND is extremely bleached. Feldspars have completely reduced with rare to minor (<2%) mafics within GND Clear qtz vns @: 137.69, 137.76, 137.87, 137.95, 138.05, 138.07. 0.25-0.50cm, @50° to CA, w/ tr. euhedral po. and trace aspy. Milky to clear qtz veins after 138.83m contain po.						
10		140.05	140.45	Unaltered GND. Minor sericite on margin of bleached GND		1				
				@ 140.35: milky qtz w/ dissem po						
10		140.45	140.80	Bleached GND w/ trace mafics. Contact w/ unaltered GND @ 45°. Tr. dissem. aspy & po appear to be vein-like in orientation, @~50° to CA, however no clear vn materials present						
10		140.80	142.49	Unaltered GND predominant w/ veining (qtz) and sericite sections as well as on fractures (from 141.85 - 142.49m pervasive). 0.5 to 1.0cm milky qtz vns w/ clear qtz centres contain trace po and aspy. Ser minor, present on margins. Vns ave at 50° to CA.						
10		142.49	143.33	Extremely bleached, sericite-rich, grey white GND. Tr. indiscernible sulphides. Core is easily scratched w/ a nail		1				
10		143.33	143.63	Both qtz veins contact CA at 35°. Disseminated aspy 2-4%. disseminated py 1-2%						
10		143.63	145.30	Extremely bleached, sericite rich, grey white GND. Tr. indiscernible sulphs. Core is easily scratched w/ a nail. At 144.10m, 0.5cm qtz vein w/ 10% disseminated po.						
10		145.30	145.56	Extremely bleached GND w/ abundant sericite adjacent to 9cm thick massive sulphide vn; 90% aspy, 10% py.						
10		145.56	147.60	Slightly green sericitic GND w/ extensive bleaching. Soft core, yet coherent. Minor 0.5-1cm qtz veining		1				
10		147.60	147.83	Fault gouge. Greenish grey clay with sulphide-looking oxidized material. No visible fresh sulphides	2					
10		147.83	148.33	Bleached and sericite rich, broken GND. Core has green sericite hue						
10		148.33	150.53	GND w/ minor sericitic partings marked by soft, green hued core. Minor carbonate veinlets. Veins: @149.37m, 149.48m, 149.52m & 149.59m, 0.25-0.5cm qtz veins with trace euhedral-subhedral po. Vns @ 40-50° to CA. At 150.16m, 150.32m, 150.38m and 150.43m, 0.5-1cm qtz veins @ 50° to CA, trace aspy.						
10		150.53	150.88	Bleached GND w/ 3 1cm qtz vns @50° to CA w/ trace disseminated aspy & po.						
10		150.88	151.20	Fault gouge, uniform light grey clay w/ minor visible qtz eyes. Appears to have ox'd sulphides mixed in, but inconclusive	1	2		5		
10		151.20	152.66	Broken GND w/ sericite-coated fracs and minor sericite partings -- Semi-decomposed GND. One 2cm qtz vein w/ no visible sulphides		3		1		
10		152.66	153.35	Highly bleached, altered GND. Abundant sericite both pervasive and on fracs. Minor sericite/clay partings		3		1		

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages											Oxidation														
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	3.0	5.5	45		10	s/chl	4														B291153	134.70	135.64	0.655		VA05045435	0.94	
3	1	1.5	3.0	50	70	12	s/chl/q	3		10.0												B291154	135.64	137.16	1.525		VA05045435	1.52	
10	1	2.5	6.0								2.0		0.1									B291155	137.16	137.69	0.359		VA05045435	0.53	
																						B291156	BLANK		<0.005		VA05045435		
6	1	0.5	3.0	50																		B291157	137.69	138.68	0.860		VA05045435	0.99	
3	1	2.0	3.3	60							2.0											B291158	138.68	140.21	0.174		VA05045435	1.53	
6	1	1.5	3.0					1			0.1											B291159	140.21	141.73	0.141		VA05045435	1.52	
6	1	1.0	4.0					1			0.1		0.1									B291160	141.73	142.49	0.206		VA05045435	0.76	
2	1	0.5	1.5					4														B291161	142.49	143.33	0.211		VA05045435	0.84	
2	1	0.5	1.5					4														B291162	142.49	143.33	0.145	DUP	VA05045435	0.84	
1		28.0								2.0			4.0	0.1								B291163	143.33	143.63	18.750		VA05045435	0.30	
2		0.5	1.0					4			0.1											B291164	143.63	144.78	0.884		VA05045435	1.15	
1		0.5	0.5					3														B291165	144.78	145.30	0.194		VA05045435	0.52	
1	6	9.0	9.0					0		10.0			90.0						0.1			B291166	145.30	145.56	1.490		VA05045435	0.26	
2	1	1.0	1.5	60	25								0.1									B291167	145.56	146.30	1.240		VA05045435	0.74	
																						B291168	146.30	147.41	0.261		VA05045435	1.11	
																						B291169	146.30	147.41	0.265	PD/CA	VA05045435	1.11	
																						B291170	STANDARD 4D		0.462	4D	VA05045435		
																						B291171	147.41	147.83	0.212		VA05045435	0.42	
																						B291172	147.83	148.83	0.091		VA05045435	1.00	
4	1	0.5	2.0	40	50						0.1											B291173	148.33	149.35	0.096		VA05045435	1.02	
4	1	1.0	3.0	50									0.1									B291174	149.35	150.53	1.550		VA05045435	1.18	
3	1	1.0	3.0	50							0.1		0.1									B291175	150.53	151.10	5.130		VA05045435	0.57	
																						B291176	BLANK		0.005		VA05045435		
1	1	2.0	2.0	50																		B291177	151.10	152.40	0.404		VA05045435	1.30	
6	1	1.0		35	50					1.0			1.0									B291178	152.40	153.92	1.840		VA05045435	1.52	

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		153.35	157.25	Mostly unaltered GND w/ qtz vns containing trace to 1% dissem sulphides, minor sericite on vn margins. At 153.34m, 153.40m, 153.60m, 153.63 and 153.71m, qtz veins 0.25-1.0cm thick, @ 35°-50° to CA contain tr-1% disseminated py, aspy. At 154.07m, a 1.5cm qtz/sulphide vein at 50° to CA contains 5% aspy and 1-2% py. At 154.12, 154.23, 154.31, 154.41, 154.43, 154.53, 153.62, 154.65, 154.70, 154.76, 154.85, 154.97 and 155.00m, 0.25-1cm thick qtz veins with trace-1% disseminated po and trace to no arsenopyrite. Average range of vn angles is 25-50° to CA. @155.42, 0.5cm thick qtz vn @50° to CA, w/ tr diss po. One 0.25cm carbonate (dolomite) vein at 156.06m, at 60° to CA contains trace py and ~1% aspy.		2		1		
10		157.25	158.01	GND becomes highly sericitized: soft, has green hue. Multiple qtz veinlets: @157.07, 157.27, 157.38, 157.42, 157.50 and 157.56m, 40-50° to CA, up to 0.5cm, max; most w/ tr. po and tr aspy.						
10		158.01	158.22	Qtz/sulphide veins and veinlet stringers within qtz veins and x-cutting throughout GND. Within the sulphide veins the py seems to always be central w/ the aspy on the margins. Dissem sulphides throughout GND section. At 158.08m, two 1-2cm thick sulphide veins at 50° to CA, contain 60% py and 40% aspy.						
10		158.22	158.50	Broken sericite abundant pervasive. Hydro-alt'd GND appears to be a fault zone. Plenty of bleached clay and qtz eyes.		3	1	3		
10		158.50	160.02	Altered, bleached GND with pervasive sericite alteration, soft core. Minor disseminations/ veinlets/ blebs of sulphides. Commonly, py~1%, as~tr.-1%						
10		160.02	160.15	Semi-massive to massive py ~99% and aspy~1%, @55-60° to CA. Some qtz veining immediately adjacent on margins.						
10		160.15	162.47	Extremely altered/sericitic. Decomposed yet coherent GND. Core has yellow/green bleached hue. Minor qtz veinlets @ 50-60° w/ tr. dissem aspy/py in half of them.		4	1	1		
10		162.47	163.50	Unaltered GND w/ veinlets of disseminated aspy (~50% of qtz vein) @40-50° to CA.						
10		163.50	165.15	Mod sericite alt'd GND. Core is mod. broken w/ occasional veinlets of qtz/dissem. sulphs. Core is v. soft and is bleached. Typical veinlets @ 50° w/ disseminated blebs of subhedral po.		4	1	1	1	
10		165.15	167.42	From 165.15-165.84m, highly altered/bleached clay. GND core is retained but pure white/grey clay veins		5		5		
10		167.42	168.13	Unaltered GND w/ sericite on fractures. Couple of qtz veins @50° to CA, w/ tr-1% po within centre of vein		1		1		
10		168.13	168.58	45cm wide milky qtz vein. Tr sulphs (indistinguishable). Contact angle is 30° to CA						
10		168.58	171.33	Moderately bleached/altered GND w/ sericite abundant on fracs. Minor sulphide/qtz veinlets. Core is moderately coherent. 3 notable veins @: 168.77, 170.10, 171.06m. Qtz veins w/ tr. dissem po and aspy, 2.5, 1, 0.5cm thick respectively. Two at 55°, last one at 80° to CA.						
10		171.33	172.21	GND is extremely bleached, but peppered w/ disseminated sulphs. Predominantly aspy (5-8%) w/ tr. py						
10		172.21	173.85	GND is moderately altered in partings and bleached white/grey. Core is mod-very broken, can't obtain angles from vein frags. Appears to be a few >1cm thick veins in section. Sericite on fracs and occasionally pervasive		2				
10		173.85	180.00	An extremely altered section of GND. Core appears as qtz/sericite and moderate chlorite. Core is silicified and all mafics are essentially altered. Some qtz veins can be seen w/ dissem. po (tr.)		3	3			
				@175.95: a clay faulted unit w/ a decomposed vn of aspy adjacent, poor core recovery. However the clay is of the graphite texture/colour w/ aspy observable. The aspy vn that remains is 1cm thick at 70° to CA. chl + ser abundant at 185.0 onward.		4	2	5		
				From 178.31 to 178.51m, qtz boudins and stringers of aspy and py. py~10%, aspy 20%. remainder of interval is of sericite and minor chl. Interpreted contact angles are 75-80° to CA.		3	1			

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

#/meter	Type	VEINS: Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages: Max. (cm)	Alteration	(0-5)	Ox. State 0-5	% of VEIN & DISSEMINATED MATERIAL: pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation: oxide	scordite	biotite	other	Sample Number	Interval: From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
16	1	1.0	7.0					2		2.0			4.0									B291179	153.92	155.31	2.850		VA05045435	1.39	
2	1	0.5	0.75	50	60						0.1		1.0									B291180	155.31	156.97	0.304		VA05045435	1.66	
14		1.0	3.5					2			0.1		0.1									B291181	156.97	158.01	0.865		VA05045435	1.04	
14		1.0	3.5					2			0.1		0.1									B291182	156.97	158.01	1.545	DUP	VA05045435	1.04	
3		0.5	1.0					3		2.0			2.0									B291183	158.01	158.50	0.622		VA05045435	0.49	
3		0.5	2.0					3		0.1	0.1		0.1									B291184	158.50	160.02	0.264		VA05045435	1.52	
3		1.5	16.0					1		99.0			1.0									B291185	160.02	160.15	8.120		VA05045435	0.13	
2		0.5	1.0					3		0.1			0.1									B291186	160.15	161.54	0.724		VA05045435	1.39	
4		1.0	2.0					3		0.1			0.1									B291187	161.54	162.47	0.236		VA05045435	0.93	
12		0.2	1.0							0.1			1.0									B291188	162.47	163.50	0.463		VA05045435	1.03	
12		0.2	1.0							0.1			1.0									B291189	162.47	163.50	0.311	PD/CA	VA05045435	1.03	
																						B291190	STANDARD 3C		0.092	3C	VA05045435		
9		0.25	1.0	50				1		0.1			0.1									B291191	163.50	164.54	1.395		VA05045435	1.04	
4		0.5	3.0	50				3		0.1			0.1									B291192	164.54	166.12	1.175		VA05045435	1.58	
5		0.75	3.0	50				1					0.1									B291193	166.12	167.64	0.368		VA05045435	1.52	
2		0.5	1.0	45				2			0.1		0.1									B291194	167.64	168.13	0.107		VA05045435	0.49	
								3														B291195	168.13	168.58	2.320		VA05045435	0.45	
																						B291196	BLANK		<0.005		VA05045435		
4		2.0	5.0	50				1		0.1	0.1		0.1									B291197	168.58	169.16	0.817		VA05045435	0.58	
3		0.25	3.0	50				2		0.1	0.1		0.1									B291198	169.16	170.69	0.741		VA05045435	1.53	
2		0.5	1.0	50				2			0.1		0.1									B291199	170.69	172.21	1.950		VA05045435	1.52	
																						B291200	172.21	173.74	0.554		VA05045435	1.53	
																						B291201	173.74	175.26	0.154		VA05045435	1.52	
																						B291202	173.74	175.26	0.228	DUP	VA05045435	1.52	
10	1	0.3	4.0	50				2														B291203	175.26	176.78	1.065		VA05045435	1.52	
																						B291204	176.78	178.31	0.348		VA05045435	1.53	
																						B291205	178.31	178.51	0.487		VA05045435	0.20	
																						B291206	178.51	180.00	0.586		VA05045435	1.49	

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From	To:		ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.00	181.57	V. minor altered GND. Sheeted qtz veins/veinlets @ ave 40° to CA w/ occasional dissem. sulphides (inconclusive type, tr po)		1	1	1		
10		181.57	182.88	Mod. altered GND. Core appears as bleached greenish hue colour, chlorite is clearly present. Core is soft. Sericite is pervasive and abundant		4	3			
10		182.88	188.98	GND broken although core recovery is 90%. Minor sericite on fracs. Predominant dissem sulph. w/in the vns is po w/ lesser amounts of aspy. Veins are sheeted and relatively constant in thickness ranging from 0.5-1cm. Qtz veins milky to clear.		1	1	1	1	
10		188.98	189.23	GND as above						
10		189.23	191.09	Fault gouge. Light, bleached remnant of former GND due to visible brecciated pieces. Core is broken adjacent to fault and then retains its former competency 20cm distally. no visible sulphides. only qtz eyes and breccia. fault angle: 40-45°						
				At 190.56m, a 5cm wide qtz vein @ 50-55° to CA w/ minor biotite inclusive, very siliceous w/ tr. po.						
				Sulphide vein @ 191.00m, 0.5cm thick, w/ 96% po and 4% aspy, @ 60° to CA.						
10		191.09	191.29	Fault zone, focussed @ 191.19m. Core increases toward fault marked by aspy and grey, ox'd aspy. Also present are slickenside surfaces in sericitized/chloritized GND. interval appears green/cream-coloured w/ mafics absent		3	3			
10		191.35	194.24	Same as above unit, however centrally the core is competent but has two 2cm qtz veins w/ dissem sulphides, at 50° to CA						
10		195.01	195.58	Silicified, bleached/altered GND. Core has white/green hue, devoid of mafics. Chlorite and sericite dominant with qtz veinlets at 50-60° to CA, w/ rare diss sulphides (po).		2	1			
10		195.58	195.64	Fault gouge w/ bleached GND. Breccia. Fault @ 50-55° to CA.		3	1	4		2
10		197.48	197.81	GND is alt'd to soft, sericite-rich and chlorite. Core is bleached and has a green hue. @197.59m, a graphite grey slickenside surface indicating faulting thus hydro fluids interpreted to alter GND to observed state, mafics almost non-existent						
				At 198.79m, a 2.5cm qtz vein @50-55° w/ tr. po. At 199.03m, 4.5cm qtz vein @40-45° w/ dissem. tr. po. At 199.91, 201.52 & 201.73m, qtz veins 2cm wide, @50° to CA with trace po.						
10		203.10	207.26	GND has abundant sheeted veins @45-50° to CA, typically 0.5-1.0cm wide, carrying ~1% po as disseminations. GND is mostly unaltered w/ v. minor sericite locals. veins spaced 5-10cm apart						
10		207.26	208.56	GND; Good recovery. Veins at 207.56m, milky white qtz, @60°, 1% cpy in vein, 30% ox'd, 0.2% aspy in margin. At 207.66m, a 3cm milky white qtz vein @70° to CA, 2% cpy, 50% ox'd. Veins at 207.74, 207.77 & 207.82m, 0.5cm, milky white @60° to CA - 1-3% cpy in vein, 30-50% ox'd, 0.2% aspy in margins. Veins at 208.48, 208.55, 208.56 & 208.61m, 0.2cm milky white qtz sheeted veins - 1% cpy in veins, trace aspy in margins.						
10		208.56	208.79	GND is bleached, grey-green colour. Sheeted vein set: at 208.60, 208.67 & 208.71m, 0.2cm, light grey qtz @ 35° to CA. Vein at 208.60m has 4cm selvage containing 3-5% po, 0.2% aspy.			2			
10		208.79	208.92	GND is brecciated, qtz frags present. 3% py (50% ox'd) present in broken qtz piece. Possible hydrothermal alt'n.						
10		208.92	209.69	GND altered to green-chlorite. Vein @ 209.09m, 2cm grey qtz @ 30° to CA, 1%py in vein, 10% ox'd. Vein @ 209.71m, milky white qtz @ 30° to CA, 15% py, 10% ox'd. Vein @ 209.42m, 1cm grey qtz @ 60° to CA, crosscut by 2cm qtz vein @ 40° to CA; 5% py in margin of crosscutting vein.			4			
10		209.69	210.39	GND altered to sugary texture. Whitish green colour. Qtz eyes present. Veins @ 209.86 @ 45° to CA, 2cm qtz vein, highly fractured, milky to grey in colour.		4				
10		210.39	211.13	mod. alt. GND, chloritic. Veins @ 210.49 & 210.80m. Milky white qtz @ 45° to CA; 0.2% aspy in vein. Core becomes highly fractured at end.			3			
10		211.13	212.14	Broken GND. Minor clay on fractures. Vein @ 211.33m, 1cm milky white qtz @ 45°						
10		212.14	212.90	GND altered to green-grey colour - chloritized. Disseminated aspy (70% ox'd) present throughout interval		1	4	1		

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages												Oxidation								Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
																						B291207	180.00	181.36	2.430		VA05045435	1.36	
																						B291208	181.36	182.88	1.000		VA05045435	1.52	
																						B291209	181.36	182.88	0.917	PD/CA	VA05045435	1.52	
																						B291210	STANDARD 2B		3.280	2B	VA05045435		
																						B291211	182.88	184.40	0.846		VA05045435	1.52	
4	1	0.5	1.0	50																		B291212	184.40	185.93	1.270		VA05045435	1.53	
5	1	0.5	3.0	45						0.1	5		0.1									B291213	185.93	187.45	0.707		VA05045435	1.52	
10	1	0.5	5.0	45	50					0.1	5		1.0									B291214	187.45	188.98	0.554		VA05045435	1.53	
8	1	0.5	3.0	45	50						2		0.1									B291215	188.98	190.50	0.110		VA05045435	1.52	
																						B291216	BLANK		0.005		VA05045435		
7	1	2.0	4.0	45	50					1.0	2		1.0									B291217	190.50	192.02	0.853		VA05045435	1.52	
1	6	0.5	0.5	60							96		4.0																
9	1	1.0	6.0	45	50					0.1	2		0.1									B291218	192.02	193.55	0.201		VA05045435	1.53	
8	1	1.0	5.0	40	50						2		1.0									B291219	193.55	195.07	0.910		VA05045435	1.52	
7	1	2.0	4.0	55	60								0.1									B291220	195.07	196.60	0.711		VA05045435	1.53	
4	1	1.0	2.5	50							1		0.1									B291221	196.06	197.48	0.781		VA05045435	1.42	
4	1	1.0	2.5	50							1		0.1									B291222	196.06	197.48	3.250	DUP	VA05045435	1.42	
3	1	0.5	1	50							1		1.0									B291223	197.48	198.12	1.625		VA05045435	0.64	
9	1	4	7	45	50					0.1	2		1.0									B291224	198.12	199.64	1.745		VA05045435	1.52	
8	1	2.5	3.5	45	50						2		1.0									B291225	199.64	201.17	1.030		VA05045435	1.53	
6	1	2	5	45	50						1		0.1									B291226	201.17	202.69	0.899		VA05045435	1.52	
9	1	1.5	4	45	55						2		0.1									B291227	202.69	204.22	3.640		VA05045435	1.53	
15	1	1	6	35	50					0.1	1.0											B291228	204.22	205.74	2.170		VA05045435	1.52	
15	1	1	6	35	50					0.1	1.0											B291229	204.22	205.74	2.350	PD/CA	VA05045435	1.52	
																						B291230	STANDARD 4D		0.459	4D	VA05045435		
12	1	0.5	6	45	50						0.1											B291231	205.74	207.26	2.190		VA05045435	1.52	
5	1	3	7	60					1.0			3.0	0.2									B291232	207.26	207.94	0.543		VA05045435	0.68	
																						B291233	207.94	208.56	2.290		VA05045435	0.62	
4	1	0.2	0.8	35		4	q	4			5											B291234	208.56	208.79	0.814		VA05045435	0.23	
3	1	2	4.5						1.0	3.0								50				B291235	208.79	209.69	2.340		VA05045435	0.90	
																						B291236	BLANK		<0.005		VA05045435		
1	1	2	2	45																		B291237	209.69	210.39	5.080		VA05045435	0.70	
2	1	1	2	45									0.2									B291238	210.39	211.13	0.553		VA05045435	0.74	
																												0.00	
1	1	1	1	45																		B291239	211.13	212.14	0.989		VA05045435	1.01	
1.0	1.0	2.0	2.0	50.0							3		1.0									B291240	212.14	212.90	0.429		VA05045435	0.76	

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From	To:		ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		212.90	213.36	More clay alteration, broken up core		1	3	2		
10		213.36	213.76	Slightly altered GND contains dissem. py. and cpy			1			
10		213.76	213.99	15cm altered zone. bleached, possible silicified. Abundant po ~5%						3
10		213.99	214.88	Unalt'd GND w/ disseminated aspy. Vein @ 214.06m, 1cm milky white qtz vein @ 50° to CA, 0.2% aspy in vein. Vein at 214.16m, 1cm milky white qtz vein @ 50° to CA, 3% po in vein.						
10		214.88	216.41	Unaltered GND. Vein@ 215.01m, 1cm, white qtz @ 60° , 5% sulphides. Vein @ 215.08m, 3cm, white qtz, @ 50°, 1% aspy in margins, 3% po and 1% cpy in vein. Veinlets at 215.47, 215.68 & 215.69m, 1% po in margins. Vein @ 216.21m, 1.5cm, white qtz, @45° to CA, 3% po in vein.						
10		216.41	217.30	GND w/ chlorite alteration around veins. Veins @ 216.56, 216.68 and 216.69m: 1cm white qtz, @60° to CA, sheeted set. 10-15% po in veins. Vein @ 217.03m, 0.2cm grey qtz at 30° to CA, 2cm selvage, 3%po, 1%cpy in vein.			2			
10		217.30	218.02	GND is fractured and altered to clay within. Minor chlorite alteration also present. Vein @ 217.39m, 1cm white qtz, @50° , 3% aspy in vein, 2cm chl selvage. Broken vein @ 217.70m, ~1cm white-milky qtz.		1	1	1		
10		218.02	218.48	Unaltered GND. Veinlets @ 217.42, 217.53 & 217.63m, 0.2cm white qtz, 5-10% po in chloritic selvages						
10		218.48	219.46	Slightly chloritized GND (1), more pronounced in vein selvages. Carbonate veins intrude fractures and qtz vein throughout interval. Vein @218.58m, 0.5cm milky calcitic qtz, @50° to CA, 2cm chloritized selvage, 1% aspy in vein. Calcite-filled fracture @218.72-218.85m.			1			
10		219.46	220.20	Weak chl alt'n in GND. Veins have strong (4) chl alt in selvages. vein @ 219.63m, 1cm milky white qtz @50° to CA, 2cm chloritic selvage, 1% py in vein, 0.2% aspy in selvage. Vein @219.67m, 0.5cm, @50° to CA, 3% po in vein. Vein @ 219.87m, 1cm qtz with carbonate filled fractures at 50°, 3% py in vein and margin. Vein @ 220.11m, 1cm milky white qtz @ 50° to CA, 3% py.			1			
10		220.20	221.08	Weak to mod (2-3) chl alteration. Veins at 220.30, 220.32 & 220.36m, 0.5cm milky white qtz @ 55° to CA, 1% aspy in veins, 1cm chl selvages. Calcite-filled fractures present.			3			
10		221.08	221.40	Unaltered GND. Vein @221.35m, 0.5cm milky white qtz, @45° to CA, 5% aspy and 6% po in vein.						
10		221.40	222.50	Strong chl alteration and carb replacement/ intrusions. Carbonate shows no preferred orientation. Dissem aspy. Vein @ 331.49m, 1cm milky white qtz @ 75° to CA, no visible sulphides.			4			
10		222.50	223.28	Same as above. Aspy present in veinlets. Fractures showing no preferred orientation and are filled with aspy (90% ox'd). Disseminated aspy also present.						
10		223.28	224.03	Unaltered GND. Vein @223.32m & 223.33m, 1cm grey qtz @ 55°, 15% po in veins. Vein @ 223.84m, 0.5cm grey qtz @ 50°, 20% po in vein. Vein @223.93m, 0.5cm, grey qtz @ 50°, 1% py in vein.						
10		224.03	225.55	Unaltered GND. Vein @ 224.30m, 0.5cm grey qtz at 110°, 1% py, 20% ox'd. Vein @224.73m, 0.5cm grey qtz w/ calcite, @ 60°, 1% po in vein. Vein @ 225.09m, 1cm milky white qtz with carbonate, 3% po. Vein @225.29m, 0.5cm milky white, 5% po in vein. Broken grey qtz vein @ 225.50m. broken qtz vein @ 225.50						
10		225.55	227.08	Unaltered GND. Veinlets @ 225.70 & 225.83m, 0.2cm, milky white qtz @65° to CA, 1% po. Vein @ 225.91m, 1cm, grey qtz, @ 65° to CA, 1cm chloritic selvage, 1% aspy in vein selvage. Vein @ 226.17m, 1cm grey qtz @ 55° to CA, 1% aspy in vein selvage, 20% ox'd. Vein @ 226.45m, 0.5cm, grey qtz, @55° to CA, 3% po in vein.						
10		227.08	228.60	Unaltered GND. Vein selvages are chloritic. Vein @227.20m, 0.5cm, grey qtz @ 55° to CA, 0-2% po. Veinlets from 227.28-227.48m, 6 milky white qtz with 1-3% po. Vein @ 227.78m, 2cm grey qtz, @55°, 2% aspy in vein. Veins @ 228.01 & 228.05m, 0.5cm grey qtz @ 65° to CA, 5-10% po in vein. Vein @ 228.46m, 1cm, grey qtz @ 60° to CA, 1% aspy in selvage. Vein @ 228.54m, 0.2cm, qtz and carbonate, @55°, 5% py in vein.						
10		228.60	229.45	Unaltered GND. Veinlets present throughout. Vein @ 229.30m, 1.5cm milky white qtz @ 60°, broken, with 3% po.						
10		229.45	230.12	Weakly chloritized GND. Core is broken up. Disseminated aspy throughout core and veinlets. Vein @229.98m, 1cm, grey qtz @ 60° to CA, 1% aspy in vein.			1			
10		230.12	230.76	Unaltered GND. Sheeted vein set: Veins @ 230.18, 230.32, 230.45, 230.50 & 230.66m. 0.2cm, grey qtz, @50°, 2% aspy in margins, 1% py in veins						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL							Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages: Max (cm)	Selvages: Alteration	Selvages: (0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B291241	212.90	213.36	0.136		VA05045435	0.46	
																						B291242	212.90	213.36	0.103	DUP	VA05045435	0.46	
																						B291243	213.36	213.76	3.430		VA05045435	0.40	
																						B291244	213.76	213.99	1.050		VA05045435	0.23	
2.0	1.0	1.0	2.0	50.0							3		0.2									B291245	213.99	214.88	0.468		VA05045435	0.89	
3.0	1.0	3.0	5.5	50.0							3	1.0	1.0									B291246	214.88	216.41	0.191		VA05045435	1.53	
4.0	1.0	1.0	3.2	60.0		2	chl	3			15	1.0										B291247	216.41	217.30	0.336		VA05045435	0.89	
2.0	1.0	1.0	2.0	50.0		2	chl	4					3.0									B291248	217.30	218.02	0.424		VA05045435	0.72	
2.0	1.0	1.0	2.0	50.0		2	chl	4					3.0									B291249	217.30	218.02	0.882	PD/CA	VA05045435	0.72	
																						B291250	STANDARD 4D		0.451	4D	VA05045435		
3.0	1.0	0.2	0.6			1	chl	4			10											B291251	218.02	218.48	0.923		VA05045435	0.46	
1.0	3.0	0.5	0.5	50.0		2	chl	4					1.0									B291252	218.48	219.46	0.553		VA05045435	0.98	
4.0	3.0	1.0	45.0	50.0		2	chl	4	1.0	3.0	3		0.2									B291253	219.46	220.20	1.210		VA05045435	0.74	
3.0	1.0	0.8	1.5	50.0		1	chl	3	1.0				1.0									B291254	220.20	221.08	0.410		VA05045435	0.88	
1.0	1.0	0.5	0.5	45.0						5			6									B291255	221.08	221.40	0.333		VA05045435	0.32	
																						B291256	BLANK		<0.005		VA05045435		
1.0	1.0	1.0	1.0	50.0																		B291257	221.40	222.50	0.224		VA05045435	1.10	
6	1	0.2	1.2	50					3				10.0									B291258	222.50	223.28	0.274		VA05045435	0.78	
3.0	1.0	1.0	2.0	55.0							20											B291259	223.28	224.03	1.310		VA05045435	0.75	
3.0	3.0	1.0	2.0	60.0							5											B291260	224.03	225.55	0.470		VA05045435	1.52	
3.0	1.0	1.0	5.0	55.0							3		1.0									B291261	225.55	227.08	0.254		VA05045435	1.53	
3.0	1.0	1.0	5.0	55.0							3		1.0									B291262	225.55	227.08	0.169	DUP	VA05045435	1.53	
3	1	2	3	55	65	2	chl	4	1		10		2.0									B291263	227.08	228.60	0.314		VA05045435	1.52	
1	1	1.5	1.5	60							3											B291264	228.60	229.45	1.070		VA05045435	0.85	
1	1	1	1	60									1									B291265	229.45	230.12	0.309		VA05045435	0.67	
5	1	0.2	1	50						1			2									B291266	230.12	230.76	1.460		VA05045435	0.64	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 19 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		230.76	232.10	GND relatively unaltered except for ~1cm selvages around 0.2cm clear qtz veins, at: 231.01, 231.05 (40°), 231.22 (40°), 231.25 (50°), 231.29 (115°), 231.33 (70°), 231.56 (70°), 231.60 (55°), 231.86 (55°), and 231.91 (60°). Surrounding the clear qtz is milky white siliceous material. There are also planes of siliceous (bleached) GND. Sulphides conc. within clear qtz or silicified areas. Conc of po @ 231.78m (10% of 1cm silicified zone).	1	2	1	1		
10		232.10	233.61	Same rock as above. Qtz veins @ 232.15 (130°), 232.29 (60°), 232.39 (60°), *232.51 (60°), *232.67 (60°), *232.86 (60°), 233.02 (45°), 233.11 (45°). Veins with * contain ~5% po. Also present in this interval are low-angle milky qtz/ ser veins.	1	2	1	1		
10		233.61	234.05	Zone of chl/ser GND. Vein at 233.82m, only 0.2cm qtz clearly visible. Surrounding rock is silicified. Po and aspy disseminated w/in 1cm of qtz. 1cm gouge zone @ 233.94m (has <2% carbonate). Silicified zone at 233.88 has po & aspy.		3	2	1	1	
10		234.05	234.15	Zone of shear and high percentage of sulphides. Highly sericitized to show good slickenside lineation on broken face - approx. perpendicular to CA, also slickens in py. Zone is v. fine-grained ox'd py in thin laminations.	3	4	2	1	1	
10		234.15	234.56	GND altered intensely - ser/chl. Only qtz grains barely visible with no real structure. Clay alteration results in break at 234.30m. At 234.56m, one small qtz vein w/ ~15% aspy ends alteration zone.	1	4	3	1	1	
10		234.56	235.70	Unaltered GND except around 0.5-1.5cm wide qtz veins, at: 234.75 (45°), 234.84 (130°), 235.05 (20°), 235.10 (70°), 235.30 (45°). Sulphides concentrated at edges of veins throughout section in random orientations, but close to 90° to CA.		1	1		1	
10		235.70	236.90	First 20cm altered ser/chl between 2 qtz veins; then unalt'd GND btwn 0.5-1.0cm qtz veins @70° to CA, at: 236.0, 236.08, 236.28, 236.46, 236.74, and 236.91m. Also: regular fracturing @ 45° approx. every 15cm.	1	2	2			
10		236.90	237.35	Moderately chl/ser alt'd GND grades to gouge/ completely sericitized section 17cm long. Two qtz veins: at 237.06 & 237.16m, 1cm and 0.5cm thick, run at 50° to CA. Po + aspy (trace) seen at margins.	1	3	2	2		
10		237.35	238.92	Unaltered GND in between milky qtz veins. Vein @ 237.42m, 45°, 1cm, w/ cpy and po. Vein @237.45m, at 45°, 0.5cm, with aspy. Vein @ 238.6m, to 45°, 3.5cm, with po.	1	1	1			
10		238.92	239.44	Unaltered GND in between milky qtz veins. Bleached (silicified) section @ 239.35m, at 30° to CA, 2.5cm thick, 3% po. Carbonate veinlets to 25° have 0.5cm selvages.	1	1			1	
10		239.44	240.85	Ser/chl altered GND. More broken rock, crumbly, sericitic (clay) pervasive to 240.0m. Qtz veins: @239.5m, 40°, 0.4cm; @239.9m, 45°, 0.3cm; @240.1m, 70°, 0.2cm; @240.23m, 45°, 1.5cm (po, trace); @240.59m, 70°, 0.5cm (aspy, trace). Gouge section 1.5cm wide at 239.5m, to 130°. Unalt'd GND after 240.0m, except veins.	2	3	1		2	
10		240.85	242.35	More altered GND due to increase in carb veinlets in random orientations and calcite veinlet to veins at low angle (20°) to CA. One 2cm wide calcite vein @ 241.63m has geode-like quality (calcite crystallized into open space), 2cm wide, at 20° to CA, reaching to 241.85m. Qtz veins also present, overprinted by and fractured at calcite veins. Qtz veins: @241.24m, 45°, 1.5cm, 2% po; @241.64m, 2° (parallel to CA), 1.2cm, tr aspy; @241.90m, 40°, 1.2cm, 5% aspy; @242.0m, 45°, 0.5cm, 10% po.	1	2			4	
10		242.35	243.84	Chl/ser/cab altered GND; no linear features can be distinguished because of alteration. Some sections of bleached rock were likely sites of qtz veins and have disseminated aspy & po surrounding them, at 242.6m, 242.85m & 243.5m. At 243.78m, a 0.5cm vein of oxidized py denotes a shear plane w/ slickenside lineations in clay minerals. Alteration halo is 6cm wide on either side.	1	4	3	1	3	
10		243.84	244.53	Barely altered GND with 5 qtz veins: @ 243.97m, 25°, 0.5cm, tr ox'd po; @ 244.08m, 70°-20°, 1cm, 5% po, tr cpy; @ 244.14m, 30°, 0.5cm, no sulphs, @ 244.18m, 20°, 1.5cm, trace py; @ 244.28m, 20°, 1.2cm, no sulphs. Slickenside sericite on frac faces. Reg fracture angles are 55° and 145°.		2	1		1	
10		244.53	244.71	Zone of greater alteration. Remnant of qtz vein 2cm long visible. Fracture to 30° shows slicken lineation of sericite + py (5%); ser is powdery (clay alt'n). High conc of carbonate veinlets (random orientations)	1	4	2	1	3	
10		244.71	246.37	Unaltered GND w/ qtz veins (3mm, clear w/ milky edge). Veins: @244.77m, 15°, 0.5cm, 2% diss po; @245.48m, 30°, 1cm, tr po, 2% aspy; @245.82m, 40°, 1cm, 5% diss po. Bleached zone @246.26m contains ~10% po and 2% aspy. Xenolith 1cm by 4.5cm long at 245.76m parallel to C.A. Monazite; has conc of bt outside its rim in GND.	1	2	1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages													Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
10	1	0.3	20	45	115						10	1.0										B291267	230.76	232.10	**2.690**		VA05045435	1.34	
3	1	1.5	5			0.5	s/q				10											B291268	232.10	233.61	**11.850**		VA05045435	1.51	
7	1	1.5	5			0.5	s/q				0																		
3	1	1.5	5			0.5	s/q				10											B291269	232.10	233.61	**11.450**	PD/CA	VA05045435	1.51	
7	1	1.5	5			0.5	s/q				0																		
																						B291270	STANDARD 5E		**1.370**	5E	VA05045435		
2	1	0.5	1	50		10	s/chl	3	0		5		5									B291271	233.61	234.05	**0.312**		VA05045435	0.44	
0										5		5	5					4				B291272	234.05	234.15	**3.390**		VA05045435	0.10	
1	1	0.2	0.2	43		1	s/q	1					15									B291273	234.15	234.56	**0.059**		VA05045435	0.41	
5	1	1.5	4	45	130.0	1	s/q	1		2		0.1										B291274	234.56	235.70	**0.922**		VA05045435	1.14	
6	1	1	4	70		10	s/chl	2		2			0.1									B291275	235.70	236.90	**0.442**		VA05045435	1.20	
																						B291276	BLANK		**<0.005**		VA05045435		
2	1	1	1.5	50		10	s/chl	4	2		0.1		0.1									B291277	236.90	237.35	**0.807**		VA05045435	0.45	
3	1	3.5	5.5	45		1	chl/s	1	0		3	0.1	0.1									B291278	237.35	238.92	**0.137**		VA05045435	1.57	
3	4	0.1	0.3	25		0.5	cb	1	1																				
																						B291279	238.92	239.44	**0.094**		VA05045435	0.52	
4	1	1.5	3	45	70	0.5	5	1	1		0.1		0.1									B291280	239.44	240.85	**0.261**		VA05045435	1.41	
4	1	1.5	3.7	45	2.0	1.0	5	1	1		12		5									B291281	240.85	242.35	**0.228**		VA05045435	1.50	
1	4	2	2	20		0.2	cb	2	1				0.1																
1	4	2	2	20		0.2	cb	2	1				0.1									B291282	240.85	242.35	**0.206**	DUP	VA05045435	1.50	
3.0	1	1	3	45		10	s/chl/cb/q	4	1		0.1		0.1									B291283	242.35	243.84	**0.797**		VA05045435	1.49	
1.0	6	0.5	0.5	45		6	s/chl/cb/q	4	1	20.0								5											
5	1	1.5	4.2	20	70.0	0.3	s/q	1	0	0.1	5	0.1										B291284	243.84	244.53	**0.053**		VA05045435	0.69	
0										5												B291285	244.53	244.71	**0.039**		VA05045435	0.18	
3	1	1	2.5			0.5	chl/s/q	1	0		10		2									B291286	244.71	246.37	**0.175**		VA05045435	1.66	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 21 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		246.37	247.76	GND unaltered except zone of carb+ser weathering at 246.89-246.96m. Qtz veins: @246.76m, 45°, 1cm; @247.07m, 25°, 1cm; @247.29m, 40°, 2cm, tr aspy; @247.60m, 45°, 1.5cm. No sulphides except as noted.		2	2	1	1	
10		247.76	249.08	Unaltered GND w/ qtz veins & silicified zones containing sulphides. Siliceous planes: @247.80m, 50°, 1cm, tr po; @248.18m, 50°, 1cm, tr po+aspy; @248.56m, 45°, 0.5cm, tr aspy; @248.66m, 45°, -.5cm, 20% po; @248.81m, 50°, 1.5cm, tr po. Qtz vein: @248.38m, 50°, 3cm, tr po.		1	1			
10		249.08	251.04	Unalt'd GND except qtz veins: @249.51m, 50°, 1cm, 10% aspy; @249.56m, 40°, 0.5cm, 5% po; @249.78m, 40°, 1cm, 5% po; @249.93m, 45°, 1.5cm, 10% po; @250.08m, 40°, 2cm, 5% po, tr aspy; @250.28m, 60°, 0.5cm, 5% po; @250.51m, 45°, 0.3cm, 5% po; @250.73m, 45°, 1cm, tr cpy.		1	1			
10		251.46	252.13	Altered/bleached GND, 3 large (3-4cm) qtz veins with diss sulphides, @251.90m, 252.10m, & 252.84m. Both chl and sericite pervasive and on fracs. Core has bleached/green hue and is soft. Core is interpreted as being hydrothermally altered		2	1			
10		252.13	255.79							
10		255.79	255.93	Unit of bleached sericitic GND. Core has green hue. Within middle (255.86m), a 2cm thick qtz vein @70° to CA, with 1-2% aspy, subhedral crystals; indicative of hydrothermal alteration of GND during qtz/sulphide emplacement.		2	1			
10		255.98	258.00	GND has become more mafic w/ increased amounts of biotite and qtz has become more cloudy/milky grey. Perhaps chlorite is having an effect at a microscopic level? Aspy is the predominant sulphide w/in the last several meters prior to E.O.H.						
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	2	4.5	45		0.5	s/q	1	0				0.1									B291287	246.37	247.76	**1.050**		VA05045435	1.39	
0																						B291288	247.76	249.08	**0.610**		VA05045435	1.32	
0.0																						B291289	247.76	249.08	**0.415**	PD/CA	VA05045435	1.32	
																						B291290	STANDARD 1A		**0.833**	1A	VA05045435		
8	1	2	5.8	45		0.5	s/chl/q	1	0		10	0.1	10.0									B291291	249.08	250.20	**0.555**		VA05045435	1.12	
																						B291292	250.20	251.19	**0.214**		VA05045435	0.99	
8.0	1.0	4.0	9.5	40.0						3.0			1									B291293	251.19	252.98	**1.210**		VA05045435	1.79	
5	1	0.5	1.5	45						0.1	0.1											B291294	252.98	254.51	**3.540**		VA05045435	1.53	
6	1	2	3	40.0	50.0								2.0									B291295	254.51	256.03	**1.280**		VA05045435	1.52	
																						B291296	BLANK		**0.006**		VA05045435		
1.0	1.0	2.0	2.0	70.0									2.0																
6	1	1	2	50	40						1		1									B291297	256.03	257.56	**0.092**		VA05045435	1.53	
1	1	1.5	1.5	45									1									B291298	257.56	258.00	**0.049**		VA05045435	0.44	
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-277C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1046m

BEARING: 000 | DIP: -50°

DATE STARTED: 27-May-05 | DATE COMPLETED: 01-Jun-05

COORD SYSTEM: NAD 27: EASTING: 459752 NORTHING: 7099315

COORD SYSTEM: NAD 83: EASTING: 459634 NORTHING: 7099497

NAD 27 (CORRECTED for historic grid): EASTING: 459722 NORTHING: 7099325

LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead

SECTION LINE 459722 (historic grid)

CONTRACTOR: Britton Brothers

SAMPLING DETAILS

Sample Sequence: B291299 to B291479

Requisition #: MASP448STRGOL.05Q | Date Shipped: 2-June-05

Lab Record #: VA05045437 | Date Received: 24-June-05

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 18.29m

Deviation:

Casing: 18.29m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

Duplicates:	B291302, B291322, B291342, B291362, B291382, B291402, B291422, B291442, B291462
Preparation Duplicate/ Check Assay:	B291309, B291329, B291349, B291369, B291389, B291409, B291429, B291449, B291469
Standards:	B291310(3C), B291330(6F), B291350(7G), B291370(2B), B291390(4D), B291410(4D), B291430(3C), B291450(2B), B291470(3C)
Blanks:	B291316, B291336, B291356, B291376, B291396, B291416, B291436, B291456, B291476

FROM	TO	LITHOLOGY
18.29	198.12	GND

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+ 27 Corr)
50	336.3	50.2	002.3	003.3
100	336.9	46.1	002.9	003.9
200	336.5	46.1	002.5	003.5

FROM	TO	ALTERATION
50	75	ox, ser, arg, cb
90	112	ox, ser, chl, arg, cb
125	150	ox, ser, chl, arg
162	198.12	ox, ser, chl, arg, cb

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

FROM	TO	MINERALIZATION (Veins)
50	55	aspy, py
64	75	aspy, py
93	97	aspy, py
120	127	po, aspy, py
130	140	po,aspy
167	185	po

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 1 of 12			
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc		Carbonate
	0 = Unoxidized	0 = Unaltered		0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered		5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-18.29			Casing						
10	18.29 - 258 (EOH)									
10		18.75	18.86	Fault gouge, clay is heavily stained by limonite, gouge contains red oxidized material, possibly hematite. Core is extremely broken and recovery is poor. Only one contact on fault can be seen. Interpreted angle of fault is @ 30° to CA.	4					
10		19.81	21.34	Within section, 2 vns, 0.75-1 cm thick of qtz @ 30-35 deg to CA can be seen. However, exact location imperceptible due to broken /poorly recovered core						
10		22.99	23.50	Core becomes sugary sand w/ heavy limonite staining, some red/brown clay (10%). no visible sulphides (difficult to constrain location due to poor core recovery). Some qtz eyes/chips are visible indicating possible veining with in section	4			1		
10		28.26	28.76	Hydrothermally altered to clay/sand. Remnant pieces of GND, sugar texture, heavy limonite staining, qtz eyes, etc. Core is severely broken, high core loss	4	2		5		1
10		28.76	35.20	no descriptions (KW)						
10		35.20	35.30	Lim stained clay zone. Zone of hydrothermal alteration as demonstrated by qtz eyes/gravel/pea-sized pieces of GND which looks to be in situ. Heavy lim, minor hematite and possible ox py.	1	2		4		1
10		36.50	37.65	Broken core; fracs w/ deep red powder (hem staining?), w/ limonite	2					
10		40.32	40.51	Clay gouge, and GND sand, qtz eyes present and clay was orange/red limonite/hematite stained indicating hydrothermal alteration either along fault surface or frac surface	2			2		
10		41.44	48.50	Possible sheeted vein system. Difficult to ascertain in areas due to core recovery and broken core, but veins appear ~ every 5 - 15cm apart and are @ 40-60 deg to CA with widths ranging from (1.5-0.5 cm) many w/ dissem aspy and po						
10		44.20	45.72	V. broken core, v. heavily encrusted by limonitic clay. Broken to sandy grvl texture.	2			3		3
10		46.05	47.00	Core appears to be silicified w/ uneven alteration of the mafics within the GND. There are sheeted clear qtz vns @ 40-45 deg to CA w/ minor diss aspy and po. Lim staining is pervasive.	3					
10		49.10	50.33	Core is extremely fractured to rubbly grvl. Heavy lim. coating. Abundant qtz pieces, possibly continuation of sheeted vn system. Section weathered to clay with some qtz eyes + mafics visible, no noticeable sulphs present.	2	1		1		5
10		50.33	51.82	Mod-Highly alt'd GND with pc's 0.1-8cm well ox'd. Relict grey qtz vn at 51.58m, 2cm wide. Totally ox'd sulphs (pyrite~5%) & hem (5%). Orientation not available (just a loose chunk).	4			1	2	
10		51.82	53.27	Increased competency, core pc's to 24cm in length. Lines of ox'd sulphs define relict qtz vns: @52.0m, 0.5cm, 35°, 15%aspy, 10%py; @52.2m, 0.4cm, 65°, 10%aspy, 5%py; @52.5m, 1.0cm, 40°, 20%aspy, 10%py; @52.6m, 0.3cm, 50°, 20%aspy, 10%py; @52.6m, 0.5cm, 50°, 5%py.	2				1	
10		53.27	53.51	Same material as 50.33m interval. No veins visible.	4			1	2	
10		53.51	54.86	Same material. One relict qtz pc. w/ ox'd py, 1cm wide, no orientation, @54.3m. Grey qtz, 1.5cm wide, 10% ox'd py @54.5m.	4			2	2	
10		54.50	54.86	Zone of extreme weathering to sand-sized particles.						
10		54.86	56.39	Same highly ox'd GND. Trace py, 90% ox'd. No veins visible.	3			1	1	
10		56.39	57.91	Red staining due to ox'd hematite on fracs. Surfaces moderately-alt'd GND. Qtz vn on 4cm$^{2\ block}$ @ 57.22m, 1.5cm wide, tr ox'd py.	3				1	

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	2 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scoordite	biotite	other	Sample Number	From	To	Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
																						B291299	18.29	19.81	0.021			VA05045437	1.52	0.411
2	1	0.75	1.50	30				1		0.1			0.1									B291300	19.81	21.34	5.380			VA05045437	1.53	0.241
2	1	1.00	2.00	35				1		0.1												B291301	21.34	22.86	0.241			VA05045437	1.52	0.626
2	1	1.00	2.00	35				1		0.1												B291302	21.34	22.86	0.259	DUP		VA05045437	1.52	
1	1							1														B291303	22.86	24.38	0.623			VA05045437	1.52	
																						B291304	24.38	25.91	1.280			VA05045437	1.53	
1	1	0.25	0.25										0.1					4.0			1.0	B291305	25.91	27.43	0.475		hematite oxidation	VA05045437	1.52	
																		4.0			1.0	B291306	27.43	28.96	0.293		quartz pieces	VA05045437	1.53	
3	1	0.25	0.75	45						0.1												B291307	28.96	30.48	0.160			VA05045437	1.52	
																						B291308	30.48	32.00	0.290			VA05045437	1.52	
																						B291309	30.48	32.00	0.266	PD/CA		VA05045437	1.52	
																						B291310	STANDARD 3C		0.087	3C		VA05045437		
1	1	1.00	1.00	45	50					0.1								4.0				B291311	32.00	33.53	0.372			VA05045437	1.53	
2	1	0.25	0.50	35	60																	B291312	33.53	35.05	0.179			VA05045437	1.52	
1	1																					B291313	35.05	35.30	0.194			VA05045437	0.25	
1	1	0.20	0.20	65					2													B291314	35.3	36.58	0.100			VA05045437	1.28	
																						B291315	36.58	38.1	0.172			VA05045437	1.52	
																						B291316	BLANK		<0.005			VA05045437		
8	1	0.50	2.50	50	55				2	0.1			1.0									B291317	38.1	39.62	0.146			VA05045437	1.52	
1	1	0.50	0.50	30					1													B291318	39.62	41.15	0.144			VA05045437	1.53	
6	1	1.50	2.50	55	60						1.0											B291319	41.15	42.67	0.276			VA05045437	1.52	
																						B291320	42.67	44.2	0.221			VA05045437	1.53	
																						B291321	44.2	45.72	0.176			VA05045437	1.52	
																						B291322	44.2	45.72	1.735	DUP		VA05045437	1.52	
10	1	1.50	5.00	40	45			1					0.1									B291323	45.72	47.24	0.350			VA05045437	1.52	
3	1	1.00	1.50	30	40			1					0.1									B291324	47.24	48.77	2.190			VA05045437	1.53	
1	6	0.50	0.50										0.1									B291325	48.77	50.33	0.184			VA05045437	1.56	
2	1	2.00	2.50							5.0								5.0				B291326	50.33	51.82	0.615			VA05045437	1.49	
5	1	1.00	2.70	50	25					10.0			15.0					5.0				B291327	51.82	53.51	1.510			VA05045437	1.69	
																						B291328	53.51	54.86	3.710		Check 1	VA05045437	1.35	
																						B291329	53.51	54.86	3.990	PD/CA	Check 1	VA05045437	1.35	
																						B291330	STANDARD 6F		2.650	6F		VA05045437		
										0.1								5.0				B291331	54.86	56.39	0.238			VA05045437	1.53	
										0.1								5.0				B291332	56.39	57.91	0.796			VA05045437	1.52	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 3 of 12		
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc	Carbonate
	0 = Unoxidized	0 = Unaltered	0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered	5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		57.91	59.44	Mod'ly alt'd GND. Disseminated ox'd py (2%) throughout section. Broken into avg 5cm chunks. Qtz vn relict @ 59.43m, 1cm wide, tr ox'd py. Carb (siderite/calcite) minor on weathered vnlet srfc's.	2				1	
10		59.44	60.96	Poor recovery (28%). Mod alt.	2					
10		60.96	62.48	Mod-highly alt'd GND	3			1	1	
10		62.48	64.01	Silicified zone (relict qtz vns): @ 62.69m, 1cm wide, 2% ox'd py, @62.50m, 40°, 1.5cm; @63.20m, 30°, 1cm, tr aspy.	2				1	
10		64.01	64.20	Zone of predominant qtz. Very broken up but vn appears to be >5cm wide. Ox'd py ~10%.	1				1	
10		64.20	65.53	Highly alt'd GND. 'Pure' gry qtz ~1cm thick seen @ 64.25m and 64.30m. Few low angle to CA vnlets of ox'd carb material.	3			1	1	
10		65.53	67.06	Qtz vns @ 65.57m, 0.5cm, 55°, 1-3cm selvage; @65.82m, 1cm, 50°, tr ox'd py; and @67.0m, 45°, 0.3cm, tr ox'd py. Fracture here has movement-induced orientation, shown in calcite. Highly alt'd zone follows, 2.5cm wide.	2			1	1	
10		67.06	67.25	Minor altered GND except on veinlet fractures, where aspy is 95% oxidized to black (scorodite). One qtz vn @67.15m w/ ox'd py (10%) concentrated at centre. Total width 0.5cm with 1cm selvage, at 60° to CA.	1				1	
10		67.25	68.58	Moderate to highly altered GND	2			1	1	
10		68.58	69.63	Competent core. Unaltered to minor ox'n alteration at 10cm alternating sections. Grey qtz veins @ 68.62, 68.65, 68.84, 68.91, 69.10 & 69.15m. Ox'd py (10%), and ox'd aspy - scorodite (~10%).	1	0	0	1	1	
10		69.63	70.10	Highly altered section. One piece clear quartz <1 cm in diameter amongst rubble	3			2	1	
10		70.10	71.00	Relatively competent core with quartz veinlets surrounded by oxidation (1cm selvage). Veinlets @ 70.15, 70.26, 70.42, 70.55 & 70.67m - width 0.2cm @ 40° to CA, contain 3% ox'd py and up to 20% aspy.	1			1	1	
10		71.00	71.63	Zone of intense alteration. Rubble; few subrounded, cloudy grey quartz pebbles.	3			3	1	
10		71.63	72.90	Poor recovery (50%). Moderately altered GND; broken up core. Oxidized on vein fractures. Internal structure lost to ox'n weathering	3				1	
10		72.90	73.60	Extremely weathered section. Clay texture with few quartz/GND chunks, up to 5 cm. Altered sericitically and oxidized to 71.25m where rock becomes more competent, to 15 cm lengths. Overall colour is light orange-brown.	4	2		2		
10		73.60	74.52	Orange-brown colour continues on relatively competent rock (20cm lengths max). Diss aspy 1% and ox py 15%. No relicts	5			1	2	
10		74.52	74.80	Extremely altered section, as at 72.9m. Intense scorodite in latter half (red brown to black). Core yellow, soft and granular.	5			2	1	
10		74.80	76.22	Highly altered section. Overall color is pale yellowish brown. ~15 rusty veinlets @ 90° to CA (0.1 to 0.5 cm) run through entire section and rusty patches up to 1cm in diameter speckle it. Py ~8%, diss aspy throughout, 2%. Scorodite on fractures + carbonate (siderite?). Clay minerals as well on fractures (powdery white).	5			1	2	
10		76.22	76.92	Extreme alteration in GND. Whole section is thick clay texture, pale yellowish brown to mustard yellow. Some remnants of GND: quartz eyes and powdery white clay alteration of feldspars. Carbonic alteration is not in clay, but in sandy areas. Patches of sericite with pearly lustre, ~2 cm, irregular shape.	5	2		4	1	
10		76.92	77.45	GND is broken to gravel size rubble. No visible qtz pieces to infer veining, but core recovery is poor.				5	1	1
10		77.45	78.10	Clay seem: rusty yellow, uniform, w/ qtz eyes. This indicates hydrothermal alt'n or faulting, poor recovery so interpretation is inconclusive. No visible sulphides however limonite is pervasive and coats broken core.						
10		78.10	81.33	Core is very broken. Few qtz vein pieces noted, carbonate veinlets are fracture-filling and are x-cutting each other but do not appear as pervasive. Lim coating on fractures continues to be abundant.				1	1	5
10		82.45	84.77	Sheeted vein unit. Vn's are increasing from 0.25cm to 2-4cm. Thick, milky vn's w/ dissem aspy (tr-1%) in half of vn's. Qtz vn's @ 40-50° to CA. Qtz vn's typically spaced ~10-15cm apart. Veins @ 82.91, 82.98, 83.15, 83.19, 83.24, 83.96, 84.16, 84.44, 84.47, 84.56 & 84.77m. Veins are 1-2cm thick, @40-50° to CA.						

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	4 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATEDMATERIAL																				
						Selvages				Sulphides									Oxidation					Interval							
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
1	1	1.00	1.00							0.1												B291333	57.91	59.44	0.111			VA05045437	1.53	
																						B291334	59.44	60.96	0.177			VA05045437	1.52	
										0.1			0.1					5.0				B291335	60.96	62.48	0.185			VA05045437	1.52	
																						B291336	BLANK		<0.005			VA05045437		
1	1	1.00	1.00	40						0.1												B291337	62.48	64.01	0.603			VA05045437	1.53	
1	1	5.00	5.00							10.0								5.0				B291338	64.01	64.2	1.630			VA05045437	0.19	
1	1	1.00	1.00	30						0.1								5.0				B291339	64.2	65.53	0.406			VA05045437	1.33	
3	1	1.00	1.80	55	45	3.0				0.1								5.0				B291340	65.53	67.06	0.449			VA05045437	1.53	
1	1	0.50	0.50	60		1.0		5	5	10.0			10.0					5.0	5.0			B291341	67.06	67.25	0.682			VA05045437	0.19	
1	1	0.50	0.50	60		1.0		5	5	10.0			10.0					5.0	5.0			B291342	67.06	67.25	0.168	DUP		VA05045437	0.19	
																						B291343	67.25	68.58	0.040			VA05045437	1.33	
6	1	0.30	1.20	40		1.0	q/s	3	1	10.0			10.0					5.0	5.0			B291344	68.58	69.6	0.624			VA05045437	1.02	
																						B291345	69.6	70.1	0.877			VA05045437	0.5	
										3.0			20.0					4.0	1.0			B291346	70.1	71	0.430			VA05045437	0.9	
																						B291347	71	71.63	0.334			VA05045437	0.63	
																						B291348	71.63	72.9	0.211			VA05045437	1.27	
																						B291349	71.63	72.9	0.200	PD/CA		VA05045437	1.27	
																						B291350	STANDARD 7G		4.470	7G		VA05045437		
																						B291351	72.9	73.6	0.416			VA05045437	0.7	
										15.0			1.0					5.0				B291352	73.6	74.52	0.088			VA05045437	0.92	
																			4.0			B291353	74.52	74.8	0.061			VA05045437	0.28	
										8.0			2.0					5.0		3.0		B291354	74.8	76.22	0.194			VA05045437	1.42	
										5.0								5.0				B291355	76.22	76.92	0.107		ox'd py diss throughout (~5%)	VA05045437	0.7	
																						B291356	BLANK		0.022			VA05045437		
																						B291357	76.92	77.72	0.281			VA05045437	0.8	
																						B291358	77.72	79.25	0.115			VA05045437	1.53	
																						B291359	79.25	80.77	0.087			VA05045437	1.52	
2	1	0.50	1.00	30	60								0.1									B291360	80.77	82.30	0.159			VA05045437	1.53	
5	1	3.00	5.00	45	50	0.3							1.0									B291361	82.3	83.82	0.324			VA05045437	1.52	
5	1	3.00	5.00	45	50	0.3							1.0									B291362	82.3	83.82	0.207	DUP		VA05045437	1.52	
										0.1												B291363	83.82	85.34	0.339			VA05045437	1.52	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 5 of 12		
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc	Carbonate
	0 = Unoxidized	0 = Unaltered	0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered	5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		85.68	86.45	At 85.68m, a 2cm thick qtz/sulphide (aspy ~1%), @40-50° to CA. At 85.85m, a 1cm thick qtz vein (milky to clear) w/ trace dissem euhedral and subhedral aspy @35° to CA. At 86.13m, a 1cm thick qtz vein @40° to CA, w/ trace diss aspy (subhedral grains) along vein margins.						
10		86.45	91.55	Brkn, rubbly, gravel sized GND, no structure visible but qtz vn pieces visible w/ tr dissem aspy						
10		89.92	91.44	V. poor recovery (22%). Broken up core, ~2cm blocks, on average. Mod alt'd GND. Two qtz vein floats 1-2cm w/ ~5% ox'd py. One coherent qtz vein w/ tr aspy on margins, trace ox'd py throughout.	1				1	
10		91.44	92.96	Mod alt'd GND. Monazite xenolith. @ 91.52m. Unalt'd patches of GND show on fresh faces, shapes irregular approx 3cm in diameter. Surrounded by brown-tinted (ox'd) GND. Regular fracture angle @75° to CA. Lim staining on fract faces. Qtz veins: @92.40m, @45°, 1cm, 5% aspy throughout, tr ox'd py; @92.60m, 50°, 0.5cm, tr aspy, tr ox'd py; @93.22m, 40°, 1cm, tr aspy, tr py; @93.32m, 45°, 1.3cm, 5% aspy (margins), tr py (ox'd).	2				1	
10		92.96	93.85	Mod→high alt'd GND. Overall colour is yellowish brown except unalt'd patches ~3cm in diameter, w/ irregular boundaries. Qtz veins: @93.30m, 35°, 0.6cm, tr aspy; @93.38, 30°, 1.5cm, 5% ox'd py; @93.42, float, 1cm, 2%py; @93.58m, 120°, 1cm, 10%aspy (50% to scor), tr py (50% ox'd).	2				1	
10		93.85	94.49	Moderately alt'd GND w/ patches of unaltered, irregular edges. Section infused w/ randomly-oriented veinlets of carbonate, oxidized to limonite. Veinlet @94.15m, to 30° is >30% sulphides (ox'd py - 90%, aspy - 10%), surrounded by unalt'd GND. Qtz vein @94.45m, 50°, w/ 10% ox'd py, 0.5cm wide. Some scor w/ lim on frac faces.	2				1	
10		94.49	96.01	Seven regular fractures throughout section @30°. Qtz veins: @95.50m, 2cm, 20°, tr ox'd py, tr aspy; @95.59m, 1cm, 45°, 10% ox'd py, diss ox'd py throughout rock from 95.59-95.85m; @95.8m, 1cm, 45°, tr po, aspy; @98.85m, 0.5cm, 45°, 5% aspy.	2				1	
10		96.01	97.54	Section mod alt'd GND. Qtz vein @ 96.11m, limonite stained, to 40°, 0.5cm, w/ 5% ox'd py. More qtz veins: @96.27m, 40°, 1cm; @96.33m, 40°, 1cm; These two veins have 1cm2 patches of aspy and surface ox'n ~7% of vein. More qtz veins: @96.60m, 1cm, 30°, tr aspy, tr ox'd py; and @96.62m, 1.5cm, 55°, tr ox'd py, tr scor'd aspy.						
10		97.54	99.15	Continuation of sheeted vn unit. Veins are typically at 40-45°, spaced10-15cm apart w/ widths ranging from 0.25-1cm thick. Veins are milky white qtz, w/ trace aspy or py sulphide disseminations. Some selvages seen but do not typically indicate ox'd sulphides, perhaps vugs. Veins: @98.16m, 0.5cm veins, @40°, tr aspy; @98.53m, 0.5cm wide, @40°, tr aspy.	1	1			0	
10		99.94	100.78	Clay alt'd GND (possible fault acting as fluid conduit). Core is severely alt'd w/ "bb sized" qtz eyes, and small sand-sized pieces of unalt'd GND, all of which are heavily lim-stained, both on surface and pervasively. Some indication of quartz veining from pieces. Clay is yellow/rust-coloured. No visible sulphides.	2	1		5		1
10		100.78	103.00	At 102.49m, a 1cm vein @35° to CA; qtz/carb vein - carb on margins, qtz 0.25-0.3cm thick within center, carrying dissem aspy (trace).		1			2	
10		103.00	109.21	From 103.0m onward, core demonstrates an obvious reduction in limonite (but still on fractures), increased competency, recovery notably higher. At 105.10m, **possible gold location**: a 2cm thick qtz vein @40° to CA, with minor pervasive limonite staining has a very faint grey qtz vein w/ py x-cutting @15-20° to CA. Sulphides noted are within the 20° vein, not in the 40° one. The 20° and 50° dip of hole makes 70° to surface which may be the gold source. The vein @ 20° was v. subtle. At 105.24m, first appearance of ox'd po dissems w/in qtz vns @50° to CA. @108.14m, a 7.5cm qtz vein at 35° to CA.	2					

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	6 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
						Selvages				Sulphides								Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
7	6	2.50	6.00	35	40								1.0									B291364	85.34	86.87	1.095			VA05045437	1.53	
3	1	0.50		40	45								0.1									B291365	86.87	88.39	0.660			VA05045437	1.52	
1	1												1.0									B291366	88.39	89.92	0.708			VA05045437	1.53	
3	1	2.00	4.00	45		2.0	q	2	2				0.1					2.0				B291367	89.92	91.44	0.230			VA05045437	1.52	
4	1	1.30	3.80	45		0.5	q	2	2	0.1			5.0					2.0				B291368	91.44	92.96	0.101			VA05045437	1.52	
4	1	1.30	3.80	45		0.5	q	2	2	0.1			5.0					2.0				B291369	91.44	92.96	0.140	PD/CA		VA05045437	1.52	
																						B291370	STANDARD 2B		3.030	2B		VA05045437		
3	1	1.50	4.10	30		2.0	q/s	3	2	2.0			5.0					2.0	2.0			B291371	92.96	93.85	0.389		%ages noted are maximums	VA05045437	0.89	
1	1	0.50	0.50	50		1.0	q/s	1	1	10.0								5.0				B291372	93.85	94.49	0.771			VA05045437	0.64	
1	6	0.50	0.50	30		1.0	q			20.0			10.0					2.0	1.0										
4	1	2.00	4.50	45	25	1.0	q	1		20.0	0.1		5.0					3.0	1.0			B291373	94.49	96.01	0.458		%ages noted are maximums	VA05045437	1.52	
5	1	1.50	6.00	40						0.1			1.0					0.1	0.1			B291374	96.01	97.54	0.122			VA05045437	1.53	
4	1	0.50	1.50	40		0.3	1		1				0.1									B291375	97.54	99.06	0.296			VA05045437	1.52	
																						B291376	BLANK		0.016			VA05045437		
																						B291377	99.06	99.94	0.167			VA05045437	0.88	
																						B291378	99.94	100.78	0.589			VA05045437	0.84	
1	3	1.00	1.00	35									0.1									B291379	100.78	102.11	0.101			VA05045437	1.33	
4	1	1.00	1.50	30	45								0.1									B291380	102.11	103.63	0.375		vein count includes sulph veins	VA05045437	1.52	
7	1	1.00	4.00	45	40					0.1												B291381	103.63	105.16	0.123		vein count includes sulph veins	VA05045437	1.53	
7	1	1.00	4.00	45	40					0.1												B291382	103.63	105.16	0.123	DUP		VA05045437	1.53	
3	1	0.25	0.75	25	35								0.1									B291383	105.16	106.68	0.366			VA05045437	1.52	
5	1	7.50	10.00	40	35						1.0											B291384	106.68	108.20	0.435			VA05045437	1.52	
5	1	0.50	2.00	40	50								0.1									B291385	108.20	109.21	0.126			VA05045437	1.01	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 7 of 12			
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc		Carbonate
	0 = Unoxidized	0 = Unaltered		0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered		5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
UNIT CODE	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		109.21	109.94	Alt'd GND. Brown/tan/rust colour. Mafics absent and replaced abundantly, with sericite and chlorite. Limonite is pervasive and on fractures, sulphides partially ox'd, where visible.	2	2	1		1	
10		109.60	110.80	Same as above, however several 1.5cm qtz veins are running within beginning and end of unit. @ 109.79, 109.90, 109.99, 110.14 & 110.24m, 0.5-1cm thick milky qtz vns, @35° to CA, w/ tr dissem aspy. @110.78, a 7cm milky qtz vein @35° to CA.						
10		110.80	111.94	no descriptions (KW)						
10		111.94	112.06	V. fine, uniform, brown clay seam, looks like chocolate ice cream. 100% clay.				5		
10		112.06	119.91	no description (KW)						
10		119.91	120.40	Slightly alt'd GND, pervasive limonite on fractures. Good recovery. Veinlets @120.08m, to 55°, 20%py.	1	1				
10		120.40	121.92	Unaltered GND with limonite in fractures. Qtz vein @ 120.51m, 3cm, milky white, 35°, 20%po. Vein @121.46m, 1cm, milky white, @45°, 20%po, 5%aspy in vein						
10		121.92	123.44	Lim pervasive in fractures. Qtz veins: @121.98m, 50°, 1cm, grey qtz, 5%po in veins; @122.39m, 50°, 1cm grey qtz, 10%po in vein; @122.46m, 50°, 1cm grey qtz, 5%po in vein; @122.92m, 45°, 1cm grey qtz, 5%po in vein; @123.44m, 50°, 1cm grey qtz, 10%po. Veinlets throughout section w/ 10%po and 5%aspy.	0					
10		123.44	124.20	Pervasive lim in fract. Moderately ox'd around veins. Veins: @123.61m, 1cm at 35°, milky white qtz, 1%aspy in margin; @123.73m, 2cm at 55°, grey qtz, 10%py in vein; @123.78m, 3cm at 55°, grey qtz, 5%py; @123.95m, 2cm at 55°, grey qtz, 20%po; @124.05m, 1cm at 55°, grey qtz, 10%po in vein, 5%aspy in margin.	0					
10		124.20	124.46	10cm qtz vein at 50°, 0.1% moly in vein. 10%py in smaller veins at 60°, cut by larger or may be offshoots.	0					
10		124.46	124.97	Mod'ly alt'd GND, pervasive lim in fractures, core is broken up. Vein @124.22m, 4cm grey qtz, at 35°, 1%aspy in margins. @120.66m and 120.83m, 1cm grey qtz at 35°.	3	2				
10		124.97	125.77	Mod alt'd GND. Vein @125.49m, 1cm milky white at 30°. No sulphides.	3	2				
10		125.77	126.98	Slightly alt'd GND. Veinlets common at 55°, 5%py. Vein @125.97m, 2cm grey qtz at 55°, 1% aspy in margins, 5% py in vein.	1	1				
10		126.98	127.57	Mod alt'd around fractures and veinlets at 60°, 5% aspy in veinlet selvage.	3	2				
10		127.57	128.02	3cm qtz vein at 55°. Grey, with 1%aspy in margin. Trends to zone of high alt'n. Clay rich with qtz eyes and GND fragments. Possibly hydrothermal alt'n or shear zone. Qtz vein near zone is fractured and offset in multiple locations - microfaults. @127.80m, 3cm zone of gouge, at 40° to CA, contains fragments of qtz vein, possible fault.	2	2	1			
10		128.02	128.45	Broken, altered GND. @128.27m, broken qtz veins in sugary GND; possible fault. @128.18m, GND alters to clay. Qtz eyes present with GND fragments - possibly hydrothermal. Vein @128.38m, 2cm grey qtz at 45°. No visible sulphides.	3	1				
10		128.45	129.54	Fractured GND w/ lim on fracts. Vein @129.05m, 1cm grey qtz at 50°, 3%aspy in vein, 80%oxidized.	1					
10		129.54	130.08	Slightly to mod'ly alt'd GND w/ disseminated aspy. Vein @129.79m, 2cm grey qtz at 35°, 3%py in vein, 1%aspy in margins.	1					

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	5 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL											Sample Number	Interval		Au (g/T)				VA05045076 Return Samples
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To				CSV	Width (m)	
2	6	3.50	5.00	50									0.1									B291386	109.21	109.73	2.070			VA05045437	0.52	
7	1	7.50	13.00	30	45								0.1									B291387	109.73	110.85	2.670			VA05045437	1.12	
																						B291388	110.85	112.78	0.095			VA05045437	1.93	
																						B291389	110.85	112.78	0.100	PD/CA		VA05045437	1.93	
																						B291390	STANDARD 4D		0.422	4D		VA05045437		
4	1	1.00	1.50	25	35								0.1									B291391	112.78	114.3	0.195			VA05045437	1.52	
2	1	0.25	0.50	30																		B291392	114.3	115.82	0.070			VA05045437	1.52	
3	1	1.50	2.00	40									0.1									B291393	115.82	117.35	0.125			VA05045437	1.53	
5	1	1.50	3.00	30		0.1	2				0.1		0.1									B291394	117.35	118.87	0.259			VA05045437	1.52	
4	1	1.00	2.00	30		0.1	2						0.1									B291395	118.87	120.4	0.151			VA05045437	1.53	
																						B291396	BLANK		<0.005			VA05045437		
5	1	3.00	5.00	35	45	2.0	q	3	2		10.0		3.0					2.0				B291397	120.40	121.12	0.810		po in vein, aspy in selvage	VA05045437	0.72	
5	1	1.00	5.00	50	45	0.0					10.0		1.0									B291398	121.12	123.44	0.442		po in vein; aspy in margins	VA05045437	2.32	
5	1	3.00	8.00	35	55	2.0	q	2	4	10.0	10.0		1.0									B291399	123.44	124.20	1.705		po in vein; aspy in margins	VA05045437	0.76	
1	1	10.00	10.00	50		5.0	chl	4	1	10.0												B291400	124.2	124.46	0.272		10% py in veinlets, tr moly in vein	VA05045437	0.26	
3	1	4.00	6.00	35		1.0	s	4	3				1.0									B291401	124.46	124.97	0.308		aspy in margins	VA05045437	0.51	
3	1	4.00	6.00	35		1.0	s	4	3				1.0									B291402	124.46	124.97	0.609	DUP		VA05045437	0.51	
1	1	1.00	1.00	30																		B291403	124.97	125.77	0.138			VA05045437	0.8	
1	1	2.00	2.00	55						5.0			1.0									B291404	125.77	126.98	0.389		aspy in margins; py in vein; abundant veinlets at 55° w/ 5+% py	VA05045437	1.21	
																						B291405	126.98	127.57	0.040		3% aspy in veinlet selvages w/ ser/chl alt'n	VA05045437	0.59	
1	1	3.00	3.00	55		1.0	q	3	2				1.0									B291406	127.57	128.02	0.304		aspy in margins	VA05045437	0.45	
2	1	2.00	4.00	45														2.0				B291407	128.02	128.45	0.608			VA05045437	0.43	
1	1	1.00	1.00	50									10.0					3.0				B291408	128.45	129.54	0.075		aspy in vein	VA05045437	1.09	
1	1	1.00	1.00	50									10.0					3.0				B291409	128.45	129.54	0.068	PD/CA		VA05045437	1.09	
																						B291410	STANDARD 4D		0.436	4D		VA05045437		
1	1	2.00	2.00	35						3.0			1.0									B291411	129.54	130.08	0.149		py in vein, aspy in margin & diss throughout interval	VA05045437	0.54	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 9 of 12		
DRILL HOLE # : DG05-277C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		130.08	131.06	Unalt'd GND. Veins, grey qtz: @130.16m, 2cm, 30°; @130.36m, 0.5cm at 50°; 10%aspy; @130.41m, 0.2cm at 50°, 1%aspy; @130.55m, 1cm at 50°, 8%py; @130.77m, 1.5cm, at 50°, 5%py.						
10		131.06	132.59	Slightly alt'd GND, limonitic fractures. Veins: @131.38m, 0.5cm grey qtz at 60°; @131.88m, 0.3cm grey qtz @50°, 10%py, @131.95m, 0.5cm grey qtz at 50°, 5%aspy; @132.00m, 2cm grey qtz @50°, 10%aspy, 3%cpy, @132.06, 0.3cm grey qtz, 5%aspy, at 50°.	1	2				
10		132.59	134.11	Unalt'd GND; lim on fractures, veinlets running at 40°.						
10		134.11	134.81	Slightly alt'd GND. Fractures at 55°.	2	2				
10		134.81	135.64	GND is bleached; <1%bt present; disseminated aspy present		2	1			
10		135.64	136.88	Lim on fractures. GND alt'd to grey-green.		1	2			
10		136.88	138.02	Core is highly fractured and broken. Clayey gouge present @ 136.91m, 137.62m, 137.91m @ 45deg to CA. Qtz eyes and broken GND in clay - possible hydrothermal or shear	2	2		4		
10		138.02	139.52	Oxidized GND @ 138.68m becomes gouge ± GND frags. Decomposed GND: qtz eyes and frags present in clay - hydrothermal or shear	2	1		2		
10		139.52	139.98	10cm qtz vein @ 30°. Vein is fractured and shows slickensides on a 30° fracture @139.60m. 5cm qtz vein @ 30° at 139.76m.				3		
10		139.98	141.05	Unalt'd GND, oxidized @139.98m to 141.05m. At 140.75m, core is altered to rust brown, minor sericite, core is weaker, yet competent, but more easily broken	2	1	1			
10		141.05	141.73	Vein @141.37m, 1cm white qtz @30°, 5% aspy, crosscut by 0.3cm grey qtz vein at 60° to CA						
10		141.73	143.26	Unaltered GND. Veins appear to be sheeted set. Minor lim on fractures. Moly found in veining at 143.06m	0					
10		143.26	144.69	Minor lim on fractures						
10		144.69	150.78	At 148.86 a 2 cm x 5cm bleb of diorite as a xenolith within GND, no chilled margin						
10		150.78	150.88	Altered zone with 3 cm qtz vein adjacent. Contact angles at 40° to CA. Core is brown with qtz eyes as breccia within brown sericite matrix. Core is soft yet competent	1	2	1			
10		150.88	159.40	no descriptions (KW)						
10		159.40	163.50	Sheeted vn system. Veins are spaced about every 5-10cm @ 35-50° to CA, with avg thickness 1cm+ . Only recognized sulphide present is diss po, trace to 1%.						
10		163.44	164.59	Altered GND Core is stained heavily (pervasively with lim) and on fractures. Core is mod'ly broken to large gravel sizes. Chlorite prevalent in section, several 3cm veins within unit which may have been conduits of hydrothermal fluids. No visible sulphides. Contact at 163.44m is marked by a 3cm vein @ 40° to CA. The 164.59m contact is less abrupt but @40° to CA, with a marked decrease of pervasive limonite easily recognized by color change and core competency.	3	1	2	0	0	
10		164.59	166.33	GND has a noticeable decrease in veins per m, core is more broken, with lim heavy on fractures, and mod to low pervasively within GND	2	1	1			

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	10 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)			Width (m)	VA05045076 Return Samples
										Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To			CSV		
5	1	2.00	5.20	50	30					8.0			10.0									B291412	130.08	131.06	0.153		aspy in vein, py in vein	VA05045437	0.98	
5	1	2.00	3.60	50						10.0			5.0									B291413	131.06	132.59	0.192			VA05045437	1.53	
7	1	1.00	2.50	40									5.0									B291414	132.59	134.11	0.050		aspy in vein and margins	VA05045437	1.52	
1	1	0.30	0.30	65																		B291415	134.11	134.81	0.157			VA05045437	0.7	
																						B291416	BLANK		<0.005			VA05045437		
3	1	1.00	1.80	30						3.0			2.0					1.0				B291417	134.81	135.64	1.065		diss aspy present in core	VA05045437	0.83	
0																						B291418	135.64	136.88	0.424			VA05045437	1.24	
1	1	2.00	2.00	50									1.0								2.0	B291419	136.88	138.02	0.151			VA05045437	1.14	
																						B291420	138.02	139.5	0.650			VA05045437	1.48	
2	1	10.00	15.00	30									20.0									B291421	139.5	139.98	9.070		aspy present in vein	VA05045437	0.48	
2	1	10.00	15.00	30									20.0									B291422	139.5	139.98	22.300	DUP		VA05045437	0.48	
4	1	1.00	3.00	45	50	2.0		3	1	5.0			10.0									B291423	139.98	141.05	1.920		Aspy in selvage, py in veins	VA05045437	1.07	
3	1	1.00	1.90	30	60								10.0									B291424	141.05	141.73	0.325		Aspy in vein and selvage	VA05045437	0.68	
5	1	1.00	2.20	35	50	1.0	q	2	1		10.0		1.0									B291425	141.73	143.26	0.031		Po found with moly in vein @ 143.06 5% moly in vein	VA05045437	1.53	
5	1	1.00	2.10	40		1.0	q	2	1		5.0		1.0									B291426	143.26	144.69	0.019		Po in vein, aspy in margin	VA05045437	1.43	
8	6	0.25	3.00	42	30	0.3		1			1.0											B291427	144.69	146.3	0.026			VA05045437	1.61	
4	1	1.00	2.00	20	35	0.5		1			0.1											B291428	146.3	147.83	0.297			VA05045437	1.53	
4	1	1.00	2.00	20	35	0.5		1			0.1											B291429	146.3	147.83	0.144	PD/CA		VA05045437	1.53	
																						B291430	STANDARD 3C		0.077	3C		VA05045437		
4	1	1.50	7.00	30	40						1.0											B291431	147.83	149.35	0.057			VA05045437	1.52	
8	1	3.00	9.00	30	45	0.3		1			0.1		0.1									B291432	149.35	150.88	0.049			VA05045437	1.53	
5	1	1.00	2.75	40	50	0.3		1					1.0									B291433	150.88	152.4	0.060			VA05045437	1.52	
10	6	1.00	10.00	35	40	0.3		1			2.0											B291434	152.4	153.90	0.066			VA05045437	1.5	
4	1	3.00	4.25	40		0.2		1			0.1											B291435	153.9	155.45	0.041			VA05045437	1.55	
																						B291436	BLANK		<0.005			VA05045437		
6	1	2.00	7.00	45	30	0.2		1														B291437	155.45	156.97	0.301			VA05045437	1.52	
5	1	0.50	5.00	40							1.0											B291438	156.97	158.5	0.039			VA05045437	1.53	
3	1	6.50	8.00	30	40						1.0											B291439	158.5	160.02	1.055			VA05045437	1.52	
9	1	3.00	10.00	32.5	40	0.2		1			1.0											B291440	160.02	161.54	0.189			VA05045437	1.52	
10	1	3.00	17.00	30	40	0.2		1			1.0											B291441	161.54	163.44	0.820			VA05045437	1.9	
10	1	3.00	17.00	30	40	0.2		1			1.0											B291442	161.54	163.44	0.280	DUP		VA05045437	1.9	
3	1	3.00	7.00	40						0.1												B291443	163.44	164.59	0.096			VA05045437	1.15	
2	1	1.50	2.00	45	50	0.3		1	2													B291444	164.59	166.12	0.040			VA05045437	1.53	
4	1	1.00	6.00	35	50	0.1		1			0.1							1.0				B291445	166.12	167.64	0.070			VA05045437	1.52	
2	1	0.25	0.50	30	40	4.0		3			0.1											B291446	167.64	169.16	0.090			VA05045437	1.52	
2	1	0.50	1.25	35	45						1.0							1.0				B291447	169.16	170.69	0.589			VA05045437	1.53	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE \\ of 12			
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc		Carbonate
	0 = Unoxidized	0 = Unaltered		0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered		5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		170.69	171.15	Chloritized, altered GND. Core is green/brown with sericite, mod soft. @170.69m, core abruptly alters with initial pervasive lim progressing to chloritization. Contact occurs parallel to central vein in unit @45° to CA. Diss aspy with vein and surrounding 10-15cm of GND (~1%).	3	2	2	0	0	
10		171.15	172.20	Lim stained core decreasing with lim only on fractures @172.20m.	1	1	0			
10		172.21	173.74	Zone of high alteration, colour orangey brown. Reg. fractures at 35° (8), limonite pervasive. Tonalite xenolith at 172.6m, approx. 2 by 5cm.	2			1	1	
10		173.74	175.26	Mod'ly alt'd GND. 1cm^2 xeno of tonalite within largest quartz vein at 174.56m.	2			1		
10		175.26	176.26	Highly alt'd GND. Fractured, colour orangey brown.	2	1		1		
10		176.26	176.78	Wide zone of qtz - 24cm. Crosscut by veinlets filled with lim (176.26m to 176.50m).	1	1				
10		176.78	177.44	Unaltered GND	0	1	1			
10		177.44	178.31	Unaltered GND w/ qtz veins	0	2	1			
10		178.31	179.83	Unaltered GND	0					
10		179.83	180.81	Altered patch, 5 by 8cm, green coloured, irregular edges, 2%po						
10		180.81	181.55	One large, branching qtz vein. Tonalite xeno 3cm by 6cm, rounded edges w/ 2mm reaction rim.		1			1	
10		181.55	183.00	Broken up GND (max length of core 20cm). Unaltered.	2	1			1	
10		183.00	184.40	Extremely altered GND. One branching qtz vein. Colour is yellowish-white. Rock is crumbly and clay-rich. Weak slickenside lineation shows on sericite/limonite fracture faces - shear zone.	4	3		2	2	
10		184.40	185.10	Fractures near parallel to CA infilled with limonite and sericite.	3	2		1	1	
10		185.10	185.50	Silt layer, med brown mud with ~5cm blocks of GND.	1					
10		185.50	186.68	Unaltered GND.						
10		186.68	188.80	Unaltered GND.	1	1				
10		188.08	189.31		2	2			1	
10		189.31	190.50	Unaltered to lightly altered GND	2	1			1	
10		190.50	192.02	Mod alt'd GND. Lim on fractures. Overall colour is whitish green w/ 0.5cm selvages	1	4	2		1	
10		192.02	192.88	GND as above. One qtz vein running nearly parallel to CA goes through core for 34cm, but is only 1cm wide. Shear/gouge section at 192.54m is approx. 2cm wide; altered to white clay texture.	1	4	2	1	1	
10		192.88	193.56	Extremely altered zone to 193.20m, where alt'n becomes moderate. Colour whitish-pale brown. Regular breaks parallel to CA (4).	4	3	0	1	1	
10		193.56	194.47	Mod'ly alt'd GND, as at 190.5m.	3	3	1	1	1	
10		194.47	195.51	Mod'ly alt'd GND, as at 190.5m	1	3			1	
10		195.51	196.60	Mod'ly alt'd GND, as at 190.5m	1	2				
10		196.60	198.12	Mod'ly alt'd GND, as at 190.5m; random fracture orientation	1	2				
				EOH						

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	12 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																						
						Selvages				Sulphides								Oxidation					Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scoordite	biotite	other	Sample Number	From	To	Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
3	1	3.00	4.00	45							0.1		1.0					1.0				B291448	170.69	172.21	0.060			VA05045437	1.52	
3	1	3.00	4.00	45							0.1		1.0					1.0				B291449	170.69	172.21	0.045	PD/CA		VA05045437	1.52	
																						B291450	STANDARD 2B		2.830	2B		VA05045437		
2	1	3.00	4.50	45		1.0	q	2	2	1.0								5.0				B291451	172.21	173.74	0.125			VA05045437	1.53	
9	1	2.00	8.00	45		5.0	q		3	0.1	5.0						0.1					B291452	173.74	175.26	14.900		moly	VA05045437	1.52	
2	1	1.00	2.00	40							3.0											B291453	175.26	176.26	0.068			VA05045437	1	
1	1	2.00	2.00	20							20.0		0.1					2.0											
1	1	20.00	20.00	45							5.0							2.0				B291454	176.26	176.78	0.220			VA05045437	0.52	
3	1	1.00	2.50	55		4.0	s/chl	3	1		10.0											B291455	176.78	177.78	0.094			VA05045437	1	
																						B291456	BLANK		<0.005			VA05045437		
5	1	1.00	3.00	50		0.5	q/s/chl	3	0		10.0	5.0							5.0			B291457	177.78	178.31	0.093			VA05045437	0.53	
3	1	1.50	2.80	30		0.4	s/q	3	0		5.0							0.0											
0																						B291458	178.31	179.83	0.041			VA05045437	1.52	
1	1	1.00	1.00	50		0.0					0.1							1.0				B291459	179.83	180.81	0.017			VA05045437	0.98	
1	1	15.00	15.00	45	15	1.0	q/s	4	0		25.0							1.0				B291460	180.81	181.55	0.052			VA05045437	0.74	
0																						B291461	181.55	183	0.019			VA05045437	1.45	
0																						B291462	181.55	183	0.024	DUP		VA05045437	1.45	
1	1	2.00	2.00	30																		B291463	183.00	184.4	0.047			VA05045437	1.4	
1	1	1.00	1.00	50		0.0																B291464	184.4	185.10	0.072			VA05045437	0.7	
0																						B291465	185.1	185.50	0.063			VA05045437	0.4	
1	1	2.00	2.00	45		0.5	q	4	0		18.0							1.0				B291466	185.5	186.68	0.103			VA05045437	1.18	
0																						B291467	186.68	188.08	0.045			VA05045437	1.4	
1	1	3.00	3.00	35		2.0	q/s	3	3	2.0	5.0							3.0				B291468	188.08	189.31	0.628			VA05045437	1.23	
1	1	3.00	3.00	35		2.0	q/s	3	3	2.0	5.0							3.0				B291469	188.08	189.31	0.717	PD/CA		VA05045437	1.23	
																						B291470	STANDARD 3C		0.081	3C		VA05045437		
1	1	1.00	1.00	45		1.0	s/q	3	1		1.0											B291471	189.31	190.5	0.025			VA05045437	1.19	
2	1	0.50	1.00	35		0.5	s/q	3	1			4.0	1.0									B291472	190.5	192.02	0.020		margins silicified	VA05045437	1.52	
1	1	1.20	1.20	50		0.0																					margins straight			
1	3	1.00	1.00	5		0.5	q/s	3	2	0.1								5.0				B291473	192.02	192.88	0.039			VA05045437	0.86	
1	1	1.00	1.00	30		1.0	q/s	3	0.5																					
0																						B291474	192.88	193.56	0.022			VA05045437	0.68	
1	3	1.00	1.00	20		0.0				0.0												B291475	193.56	194.47	0.054			VA05045437	0.91	
																						B291476	BLANK		<0.005			VA05045437		
1	1	1.20	1.20	30		0.5	cb/q	1	2	2.0	5.0						0.1					B291477	194.47	195.51	0.294		trace moly	VA05045437	1.04	
1	3	1.30	1.30	10		0.5	cb/q	3	2	0.1			0.1					5.0				B291478	195.51	196.6	0.156			VA05045437	1.09	
1	1	0.50	0.50	45						1.0	1.0											B291479	196.6	198.12	0.155			VA05045437	1.52	
1	1	3.00	3.00	30		1.0	q	1	1	2.0			0.1														aspy in selvage			
																								EOH.						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-278C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1037m

BEARING: 000 | DIP: -50°

COORD SYSTEM: NAD 27: 459713E | EASTING: 459713 NORTHING: 7099325

COORD SYSTEM: NAD 83: 459593E | EASTING: 459593 NORTHING: 7099509

NAD 27 (CORRECTED for historic grid): | EASTING: 459783 NORTHING: 7099335

SECTION LINE 459675 (historic grid)

DATE STARTED: June 1 2005

DATE COMPLETED: June 4 2005

LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 19.81m

Deviation:

Casing: 19.81m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B291480 to B291499 and B291500 to B291609

Requisition #: MASP44855STRGOL.05Q | Date Shipped: 8-June-05

Lab Record #: VA05045519 and VA05044876 | Date Received: 13-June-05

Sample Sequence: B291610 - B291631

Requisition #: MASP44855STRGOL.05Q | Date Shipped: 8-June-05

Lab Record #: VA05046431 | Date Received: 13-June-05

Duplicates:	B291482, B291502, B291522, B294542, B291562, B291582, B291602, B291622
Preparation Duplicate/ Check Assay:	B291489, B291509, B291529, B291549, B291569, B291589, B291609, B291629
Standards:	B291490 (4D), B291510 (3C), B291530 (3C), B291550 (5E), B291570 (3C), B291590 (2B), B291610 (5E), B291630 (7G)
Blanks:	B291496, B291516, B291536, B291556, B291576, B291596. B291616

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
50	334.7	-49.7	000.7	001.7
100	330	-50.6	356	357
179.83	16.3	-50.8	42.3	43.3

FROM	TO	LITHOLOGY
19.81	179.83	GND

FROM	TO	ALTERATION
26.05	80.77	Ox, ser, arg, ± cb
88.24	113.08	Ox, ser, arg
164.59	178.93	Ser, chl, arg, cb

FROM	TO	MINERALIZATION (Veins)
60.96	85.34	Py, aspy
115.82	132.82	Py, aspy, po
164.59	167.14	Cpy, py, po
178.31	179.83	Po, py

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Note: Data from reflex test at 179.83 is unreliable data

DRILL LOG LEGEND P1				DATE: June 1 - 4, 2005 PAGE 1 of 8								
DRILL HOLE # : DG05-278C				FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered			Carbonate 0 = No Effervescence 5 = Strong Effervescence				
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
	GEOLOGICAL DESCRIPTION				ROCK (Alteration)							
UNIT CODE	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
-1		0.00	19.81	Casing (no core recovery)								
10	19.81-20.25	19.81	20.25	GND / qtz and shale-like metasediments (argillite), gravel sized pieces. Unable to discern whether metaseds due to abundant qtz and granodiorite pieces, however contact / lithology change is proximal. The drill set-up appeared that collar was in metaseds (?). (poor core recovery / and v. broken core). I would interpret this to be the MSED/GND contact.	1							
80	**20.25-26.05**	20.25	23.60	MSED, core is v. broken w/ limonite staining on fracs and pervasive within foliations. Metaseds appear as dark brown to black, fine-grained, less than 1mm thick foliations which have suffered moderate silicification determined by the inability to scratch core with a nail. Foliations are, within the first few feet, at 45° - 55° to CA, with the appearance of foliation angles changing due to folding episodes at a local level. No visible sulphides present however minor hematite staining is observed on some pieces of core. Qtz pieces indicate that veins are both x-cutting and are on foliation. No visible sulphides within the qtz pieces noted. Core recovery is approx 40%. At ~20.50m, silicification diminishes and core becomes essentially argillite (core can now be scratched by a nail).	1							
80		23.60	25.00	From 23.60-23.74m, core becomes qtz eyed; clay gouge with yellow /brown coloring. Appears as hydrothermally altered, possible fault zone.	2	1		3				
80		25.00	26.05	From 25.00-25.91m, argillite has multiple vn sets within it and has thickness of veins ranging from 0.25 - 1cm thick, milky coloured. At 25.60m, 2 vns x-cut each other at 35° and 155-160° to CA. No visible dissem sulphides present. Limonite on fractures but less pervasive on foliation. Core section was poor core recovery but competent core pieces were available for logging.	1							
10	**26.05-65.53**	26.05	30.48	Granodiorite/argillite contact, GND continues on. Core is broken to rubbly gravel; few structural bits intact for logging, lots of qtz pieces.	1			1				
10		30.48	32.00	GND altered to sand-sized pieces. Core is not bleached, heavy limonite staining. Visible qtz pieces indicating veins present. Minor clay mostly sand, mafics easily visible. Core essentially looks weathered to rotten.	2			1				
10		32.00	33.53	Core recovery is poor and core is extremely broken, however it appears as though there is a sheeted qtz vein system occurring, due to the abundance of qtz pieces in the rubble. No visible sulphides noticed w/ in the qtz pieces. Heavy limonite on fracs and pervasive.	2			1				
10		33.53	35.20	Core recovery is very low however several episodes between gravel pieces to clay sections w/ qtz eyes w/ heavy limonite straining on fracs and pervasive. Hydrothermal alteration is evident throughout this particular section, no sulphides noted. Clay is rusty brown and uniform. Remaining core is of sandy gravel consistency.	2			2				
10		35.20	38.10									
10		38.10	39.62	Core has same characteristics as above (33.53-35.20m). Possible hematite staining on fracs.	2			1				
10		39.62	41.15									
10		41.15	44.20	Highly digested GND, mafics intact but core is abundant w/ sericite. Core is salt/pepper in appearance & crumbles when touched. No coherency. Limonite is extremely pervasive & on fracs. Minor 10-15cm units of rusty coloured clay seems very indicative of hydrothermal alt'n.	3	1		1				
10		44.20	45.72	Core becomes much more competent, but limonite on frac/selvages & is pervasive. Ox'd py w/in some vns/vnlets pieces show red rust blebs (may be well-ox'd pyrite).	1							
10		45.72	47.24	Core is extremely broken w/ poor core recovery. Core is sandy gravel in texture w/ v. abundant limonite & bits of ox'd py. Some clay seems relict.	3	1		1				
10		47.24	48.77	Core is essentially a clay gouge. Alt'n zone - Core in places is somewhat preserved, mafics are intact w/ limonite & sericite on fracs & pervasively. Qtz eyes visibly intact. Some indications of veins. Minor hematite staining & ox'd py pieces w/in qtz pieces.	3	1		3				
10		48.77	53.61	Core is extremely broken to sandy gravel or to clay seams. Core recovery is ~50-65%. Limonite is pervasive & abundant, sericite is on fracs & w/in selvages. Mafics are still intact & highly ox'd py can be seen as relict orangey-red blebs on qtz pieces & in broken pieces of core.	4	3		2				
10		53.61	55.53									
10		55.53	55.58	Clay seam w/ qtz eyes, clay is of rusty uniform color. Minor reddish staining on 55.58m contact surface indicating ox'd py (essentially an alt zone).	3	1		4				
10		55.58	55.80									
10		55.80	59.44	Core is very uniformly hydrothermally alt'd to soft, mushy, sandy clay w/ heavy pervasive limonite. Sericite is observed in relict selvages & fracs. Qtz eyes 'bb'-sized abundant. Core looks like it has been digested by meteoric waters. Some reddish blebs & stains reminiscent of former py, not a lot of visible vns. Mafics are preserved where clay is less abundant. Core loss is @ ~80%, thus good representation of actual unit.	5	3		4				
10		59.44	60.96	GND altered to clay/crumbly texture. Colour is orangey-pale brown. Aligned qtz pebbles denote old veins. Carbonate is siderite >calcite.	3	1		3	2			
10		60.96	62.48	Qtz eyes and relict feldspars left in crumbly mess. Ox'd hematite present. Sericite aligned at ~15° to CA	4	2		2	2			
10		62.48	64.01	Colour whitish yellow to orangey brown. Qtz vein at ~62.9m, grey qtz.	3	2		3	2			
10		64.01	65.41	Colour a more medium-dark brown. Crumbly-clay gouge GND. Clear-milky qtz veins	4			3	2			
10		65.41	65.53	Large qtz vein w/ lim on fractures. Diss ox'd py throughout. Ox'd hematite present ~3%	1				1			
90	**65.53-66.00**	65.53	66.00	Qtz vein at 65.53m. Section is argillite (MSED); fine mafic laminations define meta-beds. Felsic section at 65.7m (QZZ) with diss ox'd py, muscovite (15%). Microfolds visible on the cm/mm scale. Ox'd hematite (10%) in mafic sections.	4	1		4	1			
10	**66.00-179.83**	66.00	67.06	Clay to crumbly GND. Largest pieces ~2cm square. Clear qtz pebbles noted at 3 depths	4	1		3	2			
10		67.06	68.58	Highly to extremely altered GND. First 20cm is somewhat coherent core (10cm chunks). After that gouge-clay texture. More competent GND below qtz vein relict, for ~10cm. Gouge to end.	4	3		3	2			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
2	1	0.25	0.5	40	45	0.1		1														B291480	19.81	21.34	<0.005			VA05045519	1.53
2	1	0.50	1.0	35	40	0.1		1														B291481	21.34	22.86	0.005			VA05045519	1.52
2	1	0.50	1.0	35	40	0.1		1														B291482	21.34	22.86	0.014	DUP		VA05045519	1.52
1																						B291483	22.80	24.38	0.027		pieces	VA05045519	1.58
5	1	1.00	3.0	25	35	0.1		1														B291484	24.38	25.91	0.041			VA05045519	1.53
4	1	2.00	2.0	50				1														B291485	25.91	27.43	0.019			VA05045519	1.52
																						B291486	27.43	28.96	0.060			VA05045519	1.53
2	1	0.75	2.0	50		1.0																B291487	28.96	30.48	0.226		greater than 2	VA05045519	1.52
1																						B291488	30.48	32.00	0.376		qtz pieces only	VA05045519	1.52
1																						B291489	30.48	32.00	0.478	PD/CA		VA05045519	1.52
																						B291490	STANDARD 4D		0.239	4D		VA05045519	
4	1	0.75	3.0	40				2														B291491	32.00	33.53	0.972		4 and qtz pieces	VA05045519	1.53
1																						B291492	33.53	35.05	0.281		qtz pieces only	VA05045519	1.52
1																						B291493	35.06	36.58	0.470		qtz pieces only	VA05045519	1.52
3																						B291494	36.58	38.10	0.114		2 and qtz pieces	VA05045519	1.52
1																						B291495	38.10	39.62	<0.005		qtz pieces only	VA05045519	1.52
																						B291496	BLANK		0.396			VA05045519	
1																						B291497	39.62	41.15	0.843		qtz pieces only	VA05045519	1.53
2	1			35																		B291498	41.15	42.67	0.636		1 vein + qtz pieces	VA05045519	1.52
2	1			40	45	0.1		1														B291499	42.67	44.20	0.779		1 vein + qtz pieces	VA05045519	1.53
7	1	0.50	3.0	40	50	0.1		1		0.1								3.0				B291500	44.20	45.72	0.184		tr hem	VA05044876	1.52
1										0.1							0.1	3.0				B291501	45.72	47.24	0.886		tr hem; qtz pieces	VA05044876	1.52
1										0.1							0.1	3.0				B291502	45.72	47.24	0.234	DUP		VA05044876	1.52
										0.1							0.1	3.0				B291503	47.24	48.77	0.248		tr hem	VA05044876	1.53
1										0.1								2.0				B291504	48.77	50.29	0.134		qtz pieces	VA05044876	1.52
2	1			45	50					0.1								2.0				B291505	50.29	51.82	0.117		qtz pieces	VA05044876	1.53
4	1	1.50	3.0	45	50					0.1								4.0				B291506	51.82	53.34	0.302			VA05044876	1.52
2	1	1.00	1.5	55	60					0.1			0.1					4.0				B291507	53.34	54.86	0.156		qtz pieces	VA05044876	1.52
1										0.1								5.0				B291508	54.86	56.39	0.768		qtz pieces only	VA05044876	1.53
1										0.1								5.0				B291509	54.86	56.39	4.170	PD/CA		VA05044876	1.53
																						B291510	STANDARD 3C		0.091	3C		VA05044876	
										0.1								5.0				B291511	56.39	57.91	0.221		clay	VA05044876	1.52
										0.1								5.0				B291512	57.91	59.44	0.128		clay	VA05044876	1.53
										0.1								5.0									clay		
2	1	1.00	2.0	45						0.1								5.0				B291513	59.44	60.96	0.263			VA05044876	1.52
2	1	1.50	2.0	50						3.0								5.0				B291514	60.96	62.48	0.571			VA05044876	1.52
1	1	3.00	3.0	45						2.0								5.0				B291515	62.48	64.01	0.111			VA05044876	1.53
																						B291516	BLANK		<0.005			VA05044876	
2	1	2.50	3.0	50						0.1								5.0				B291517	64.01	65.41	0.358			VA05044876	1.40
1	1	12.00	12.0	45						3.0								5.0				B291518	65.41	65.53	0.166			VA05044876	0.12
1	1	5.00	5.0							7.0								5.0				B291519	65.53	66.00	1.210		pieces only, angles indeterminable	VA05044876	0.47
3	1	1.00	3.0							0.0												B291520	66.00	67.06	0.060		pieces only, angles indeterminable	VA05044876	1.06
1	1	3.00	3.0							2.0	1.0							5.0				B291521	67.06	68.58	0.092		pieces only, angles indeterminable	VA05044876	1.52

DRILL LOG LEGEND P1				DATE: June 1 - 4, 2005 PAGE 3 of 8								
DRILL HOLE # : DG05-278C				FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered			Carbonate 0 = No Effervescence 5 = Strong Effervescence				
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
	GEOLOGICAL DESCRIPTION				ROCK (Alteration)							
UNIT CODE	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
10		68.58	70.10	Mod. to highly altered GND. Core coherent from 69.15m with only minor clay alt'n. Oxidation throughout. Colour pale brown.	4	3		2	2			
10		70.10	71.63	Grades from competent (but mod. altered) to highly altered GND. Diss ox'd py throughout section (one patch 1cm^2 near qtz vein)	4	4		2	2			
10		71.63	73.15	Colour orangey pale brown. Core fairly competent, recovery good (89%).	2	1		2	1			
10		73.15	79.25	Mod - highly-altered GND. Colour white-pale brown. Qtz, feldspars, and most bt still in situ with some (30%) alt'n of feldspars to clay (opaque, white) minerals. Matrix material all altered. Qtz veins overprinted by alteration, so they are broken and little to no selvage present. Qtz veins broken and selvage overprinted by alt'n.	3	2		3	1			
10		79.25	80.77	Moderately to highly altered GND trending to gouge @ 79.33-79.67m. Gouge contains decomposed GND frags and a possible remnant quartz vein. 5cm broken qtz vein @ 79.92m	2	1		2				
10		80.77	81.52	Core broken into fragments up to 6 cm, becoming more altered to sericite @81.13 -81.37m. 4cm fractured and oxidized grey qtz with carb vein @81.30m.	1	3		2				
10		81.52	82.55	Clayey gouge dominant with 9cm section of moderately altered GND @82.30m	1	2		3				
10		82.55	83.82	Slightly altered GND with lim on fracs. Core is highly fractured and broken. Fractures predominantly @ 80-85° to CA	1							
10		83.82	85.34	Moderately altered, less fractured and broken. Lim on frac. @83.71m, 2cm clayey gouge @ 45° to CA - shear.	2	1		1				
10		85.34	86.87	Less altered, becoming broken and clay rich @85.94m. Broken qtz veins present in clays, appear offset --possible small scale fault/shear.	1			3				
10		86.87	87.40	Slightly altered GND, more competent	1							1
10		87.40	87.77	Zone of fractured and offset qtz veins. Offset sinistrally @50°.	1							
10		87.77	88.24	Unaltered GND trending to carb alt'n after 87.98m	0	1			3			
10		88.24	88.92	Ox'd GND. Qtz veins offset @50°, appears sinistral. Lim on fractures.	2			1				
10		88.92	91.44	Core fractured at 50°, same as the offset angle of the quartz veins								
10		91.44	94.49	Moderately altered GND with lim on fractures. GND has sugary, mushy texture with higher clay content towards end of interval. Qtz veins are fractured or broken.	2			3				
10		94.49	96.01	Intensely altered to clay from 94.49-94.79m. @94.79 ~1m shear zone. Lineation @130°. Winged porphyroblast @96.46m, parallel to lineation direction and shows a sinistral rotation, indicating shear sense. Qtz vns present are broken and sheared. Shear zone is grey-green.	2			1				
10		96.01	96.14	Clay gouge, qtz eyes present - possible hydrothermal alteration, likely related to shear zone above.	1			3				
10		96.14	96.68	Moderately altered GND	1	1		3				
10		96.68	98.28	Broken GND, lim staining, sugary texture. Qtz veins are broken.	2			3				
10		98.28	99.06	Moderately altered GND								
10		99.06	99.68	At 99.06m is a 4cm clay gouge - fault/shear zone. Then, moderately altered GND, lim on frac, more competent than above. Fractured @ 99.48m.								
10		96.68	100.58	Broken GND. Lim on frac								
10		100.58	101.58	Unaltered GND. Fragmented @ 101.46m. Vein @ 100.96m.								
10		101.58	102.11	GND fragmented until 100.68m, becomes fractured w/ lim on fracs								
10		102.11	102.73	Mod'ly alt'd GND. Pervasive lim	2	1		2				
10		102.73	103.63	Broken GND frags (max 6cm). Lim on frac.	1							
10		103.63	103.94	Mod alt GND. Reddish brown colour	3							
10		103.94	104.43	Less altered	1							
10		104.43	105.36	Intensely altered GND. Sugary texture, qtz eyes present w/ GND frags. Qtz veins fractured and offset	3	2		2				
10		105.36	110.51	Intensely altered GND. Core is yellow-beige w/ rusty patches. Qtz eyes, bt and GND frags present in clay. Veins are fractured or broken. Hydrothermal alt'n on shear zne. No obvious lineation or orientation indicators	2	2		3				
10		110.51	111.88	Slight to mod alt'n in GND. Core is fractured w/ pervasive lim as well as on fracs	2	2		1				
10		111.88	113.08	Core is fractured and broken. Qtz veins present, but broken	2	1		1				
10		113.08	114.44	Mod'ly alt'd GND. Sugary texture; becomes more altered to clay @114.12m	1	1		2				
10		114.44	115.52	Fractured GND. Lim on fracs	1							
10		115.52	115.82									
10		115.82	116.83	Mod'ly alt'd GND. Overall colour is med brown w/ alignments of yellow clay minerals (w/ sulphur?). Limonite, including siderite, on fracs	4	1		2	1			
10		116.83	117.90	Minor alt'n in GND. Veinlets noted here because they're different in appearance - straight w/ large selvages; Set of 2 veinlets @117.45 to 117.50m	1	1			1			
10		117.90	119.06	Minor alt'n in GND. Qtz/carb veins have large selvages. Shear sense indicator (drawn), sinistral movement.	1	1	1		3			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2006

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	3.00	3.0							2.0	1.0							5.0				B291522	67.06	68.58	0.087	DUP		VA05044876	1.52
1	1	1.50	1.5	35	145	0.2	lim	3	4		0.1		0.1									B291523	68.58	70.10	0.118			VA05044876	1.52
1	1	0.50	0.5	70		0.2	lim/q	3	4	0.0								0.0				B291524	70.10	71.63	0.153			VA05044876	1.53
3	1	1.00	3.0	45		1.0	q	3	1	2.0			5.0					5.0				B291525	71.63	73.15	0.599		aspy in margins, py in vein	VA05044876	1.52
1	1	3.00	3.0	50																		B291526	73.15	74.50	0.251			VA05044876	1.35
																						B291527	74.50	75.71	0.199			VA05044876	1.21
																						B291528	75.71	76.20	0.066			VA05044876	0.49
																						B291529	75.71	76.20	0.124	PD/CA		VA05044876	0.49
																						B291530	STANDARD 3C		0.844	3C		VA05044876	
3	1	1.00	3.0	45						0.1			1.0									B291531	76.20	77.72	0.297			VA05044876	1.52
1	6	0.20	0.2	30	0					25.0			5.0					4.5				B291532	77.72	79.25	0.434			VA05044876	1.53
3	1	1.30	3.3	35						10.0			2.0					5.0											
2	1	5.00	5.5	50	60	0.0							1.0									B291533	79.25	80.77	0.326			VA05044876	1.52
1	3	4.00	4.0	40		0.0																B291534	80.77	81.52	0.349			VA05044876	0.75
0																						B291535	81.52	82.55	0.094			VA05044876	1.03
																						B291536	BLANK		<0.005			VA05044876	
0																						B291537	82.55	83.82	0.070			VA05044876	1.27
3	1	1.00	2.0	60									1.0					5.0				B291538	83.82	85.34	0.276			VA05044876	1.52
1																						B291539	85.34	86.87	0.051		broken and fragmented	VA05044876	1.53
1	1	1.00	1.0	45		1.0	chl/q	4	1				1.0									B291540	86.87	87.40	0.127			VA05044876	0.53
2	1	2.00	4.0							3.0			1.0					2.0				B291541	87.40	87.77	0.060			VA05044876	0.37
2	1	2.00	4.0							3.0			1.0					2.0				B291542	87.40	87.77	0.153	DUP		VA05044876	0.37
5	1	3.00	4.5	50		1.0	q	3	1		5.0	3.0	3.0					3.0				B291543	87.77	88.24	1.965			VA05044876	0.47
2	1	1.00	2.0	70									2.0									B291544	88.24	88.92	0.177			VA05044876	0.68
5	1	1.00	3.5	60		2.0	chl	3	1				3.0					1.0				B291545	88.92	91.44	0.150			VA05044876	2.52
2	1																					B291546	91.44	92.96	0.082		Veins are broken and fractured, unable to get orientation information	VA05044876	1.52
																						B291547	92.96	94.49	0.146			VA05044876	1.53
1	1					6.0							1.0									B291548	94.49	96.01	0.042		qtz veins present, but orientation unrecognizable due to shear	VA05044876	1.52
1	1					6.0							1.0									B291549	94.49	96.01	0.048	PD/CA		VA05044876	1.52
																						B291550	STANDARD 5E		1.475	5E		VA05044876	
																						B291551	96.01	97.54	0.110			VA05044876	1.53
2	1	3.00	4.0	45		0.0							0.1									B291552	97.54	99.06	0.183			VA05044876	1.52
1	1	1.00	1.0	50		0.0							1.0									B291553	99.06	99.68	0.351			VA05044876	0.62
2	1	1.00	2.0	50		0.5	q	3	1				2.0					4.0				B291554	99.68	101.58	0.035			VA05044876	1.90
2	1	0.30	0.6	50		0.1	q	2	2		3.0		5.0					4.0				B291555	101.58	102.73	0.300			VA05044876	1.15
																						B291556	BLANK		<0.005			VA05044876	
1	1	0.30	0.3	35									1.0					5.0				B291557	102.73	103.63	0.085			VA05044876	0.90
4	1	1.50	2.1	45								1.0						5.0				B291558	103.63	104.43	0.049			VA05044876	0.80
1	1	1.00	1.0	55		1.0			3	2.0								4.0				B291559	104.43	105.36	0.339			VA05044876	0.93
																						B291560	105.36	106.68	0.055			VA05044876	1.32
																						B291561	106.68	108.20	0.121			VA05044876	1.52
																						B291562	106.68	108.20	0.044	DUP		VA05044876	1.52
																						B291563	108.20	109.73	0.092			VA05044876	1.53
																						B291564	109.73	110.51	0.039			VA05044876	0.78
4	1	2.00	4.0	40									3.0					5.0				B291565	110.51	111.88	0.099			VA05044876	1.37
1	1												1.0					4.0				B291566	111.88	113.08	0.084			VA05044876	1.20
1	1																					B291567	113.08	114.44	0.308			VA05044876	1.36
1	1																					B291568	114.44	115.85	0.017			VA05044876	1.41
1	1																					B291569	114.44	115.85	0.018	PD/CA		VA05044876	1.41
																						B291570	STANDARD 3C		0.091	3C		VA05044876	
1	1	0.50	0.5	25		2.0	q/s	3	4	0.0								0.0				B291571	115.82	116.83	0.061		first vein straight second branching	VA05044876	1.01
1	1	5.00	5.0	30		1.0	q/s	2	3	5.0			2.0					5.0	1.0										
3	1	2.50	5.0	25	40	3.0	q/s	3	2	3.0			1.0					4.0	3.0			B291572	116.83	117.90	0.077			VA05044876	1.07
2	1	0.20	0.4	35		2.0	q	3	1				2.0																
4	3	1.00	2.0	50	30	17.0	q/s/chl	4	1	15.0			0.1					5.0				B291573	117.90	119.06	0.020			VA05044876	1.16

DRILL LOG LEGEND P1				DATE: June 1 - 4, 2006 PAGE 5 of 8							
DRILL HOLE # : DG05-278C				FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered				Carbonate 0 = No Effervescence 5 = Strong Effervescence		
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93											
	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
UNIT CODE	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
10		119.06	120.24	Unaltered GND where selvage from large qtz veins not affecting	1	1	1		1		
10		120.24	120.67	Mod'ly alt'd GND	1	2	1	1			
10		120.67	122.09	Unaltered GND. Lim on fracs	1	1					
10		122.09	123.63	Unaltered GND. Lim on fracs; sericite weathered to clay minerals on fracs	1	1		1			
10		123.63	124.97	Minor to unaltered GND. Po. Is pale bronzy silver coloured. Highly altered section (ser=1, chl=3, carb=3), from 123.80 to 124.00m.	1	2			1		
10		124.97	126.49	Unaltered section of GND w/ 7 congruent qtz veins. Aspy/scor concentrated at margins of straight, narrow veins. Some calcite along veins as well (~10%). 5cm x 3cm bleb of alt'd GND, to dark grey. Bt crystals still visible, few small (2mm) qtz crystals as well. Weakly magnetic; Hematite/magnetite(?) @125.18m.					1		
10		126.49	128.02	Unaltered GND except selvages					1		
10		128.02	128.68	GND dominated by silicified selvages of qtz veins. ~10cm gaps between selvages are unaltered. Selvage contains lots of dissem aspy and po.							
10		128.68	128.97	Silicified zone abuts unaltered GND @ 10° to CA. Diss aspy/scor and po. If qtz vein *was* here, it's not visible (possibly just outside core range).							
10		128.97	130.55	Unaltered GND. Qtz veins begin at 129.92m.							
10		130.55	131.44	Unaltered GND. Narrow silicified vein branches w/ scorodite/aspy and minor py. Minor lim on fractures.							
10		131.44	132.36	Unaltered GND							
		132.26	133.10								
10		133.10	133.85	Chlorite alteration zone. Core is bleached to white and green "speckled" core w/ a 3cm qtz vein @35-40° to CA. V. tr aspy disseminated w/in vein material. Mafics are completely depleted		3	3				
10		133.85	142.95								
10		142.95	144.49	Core is altered to a limonite/rusty brown; core is soft yet coherent, sericite and limonite are pervasive. Some clay ~1 3%	2	1		1			
10		144.49	148.38	White, soft carbonates are fracture filling into competent GND. Essentially x-cutting/carbonate stringer veinlets					1		
10		148.38	149.35	GND is fractured / healed w/ carbonate veinlets. Veinlets are gouge - soft and pure flour white.					1		
10		149.35	152.40								
10		152.40	154.40	GND as previous unit (148.38-149.35m), except that some carbonate vns are thicker (~0.25cm) and are running parallel to C.A. No visible sulphides disseminated within the calcite / carbonate vns/vnlets.					1		
10		154.40	158.50								
10		158.50	160.02	GND is oxidized slightly w/ pervasive limonite, minor sericite (both as fracture filling and somewhat pervasive). Core is rusty yellow/brown yet competent.	2	1			1		
10		160.02	163.70	Sheeted vn system appears. Vns are regular and similar. Vns are ave. 0.5-3.75cm in width. They have regular spacings of ~ 5-15cm apart @ an ave angles of 35-40°. Predominant noted sulphide is pyrrhotite @ tr-2%, as disseminations within the vns.		1	1				
10		163.70	164.59								
10		164.59	165.60	Mod'ly alt'd GND. Overall colour is pale whitish green with uneven patches, up to 10cm long of less altered GND, which is pale grey. One straight fracture face (25° to CA) is covered with powdery black alt'n product with various diss. sulphides (aspy, cpy and chalcocite (?) - striated dull gold colour + black granular aggregates), 0.5cm wide, at 165.18m.		3	3	1			
10		165.60	166.86	Unaltered except for wide selvages around qtz veins at beginning of sample. At least minor sericite throughout entire sample.		2	2		1		
10		166.86	167.14	14cm qtz vein: translucent milky white. Selvage also included in sample (total: 28cm).							
10		167.14	168.22	Alt'n is minor but rock is very broken up; fractures near parallel to CA and at ~80° to CA.		2	1		1		
10		168.22	169.43	Minor to mod alt'n in GND. Near-parallel fractures still prevalent but rock is more competent (less high-angle fractures).		3	2		1		
10		169.43	170.96	Minor to mod alt'n in GND. Massive sulphides (vein) beside qtz vein at 170.75m - noted on sample ticket. Minor diss sulphides throughout section (aspy, po).		3	3				
10		170.96	172.56	Extreme alt'n here. Whole sample is gouged out clay material with ~40% remnant GND material: qtz eyes, hb crystals (~2mm), etc.	2	2		4	2		
10		172.56	173.74	Mod'ly alt'd GND. Colinear fractures at 50° to CA (?).		3	1	2	1		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	4.00	6.0	20	30	15.0	q/s/chl	4	5		8.0							3.0				B291574	119.06	120.24	0.077			VA05044876	1.18
1	1	0.40	0.4	50		2.0	q/s/chl	2			2.0											B291575	120.24	120.67	0.640			VA05044876	0.43
																						B291576	BLANK		<0.005			VA05044876	
2	1	0.30	0.6	35		1.0	q/s	3			3.0											B291577	120.67	122.09	0.032			VA05044876	1.42
5	1	1.20	3.6	30	40	1.0	q/s	2			10.0											B291578	122.09	123.63	0.095			VA05044876	1.54
5	1	1.30	5.0	45		0.5	q/s	2		2.0	3.0							5.0				B291579	123.63	124.97	0.018			VA05044876	1.34
7	1	1.50	5.5	30	40	1.0	q/s/cb	3			10.0		5.0					2.0	5.0			B291580	124.97	126.49	0.164			VA05044876	1.52
2	1	0.80	1.4	10		1.0	q	3			0.1		5.0									B291581	126.49	128.02	0.341			VA05044876	1.53
11	1	1.30	4.0	40	50	1.0	q/chl	3			10.0	0.1	5.0						3.0									VA05044876	
11	1	1.30	4.0	40	50	1.0	q/chl	3			10.0	0.1	5.0						3.0			B291582	126.49	128.02	0.087	DUP	1 vein @50°	VA05044876	1.53
5	1	0.70	2.5	20	30	10.0	q	4			10.0	1.0	15.0							1.0		B291583	128.02	128.68	0.319		1 vein @30°	VA05044876	0.66
											20.0		20.0						3.0			B291584	128.68	128.97	0.029			VA05044876	0.29
6	1	0.50	2.4	30	40	1.0	q	3		5.0			10.0						3.0			B291585	128.97	130.55	0.024			VA05044876	1.58
										10.0			10.0						4.0			B291586	130.55	131.44	0.032			VA05044876	0.89
3	1	0.30	0.9	25	45	1.0	q	3		20.0			5.0					4.0	2.0			B291587	131.44	132.36	0.050			VA05044876	0.92
6	1	1.25	6.0	20	45						5.0											B291588	132.36	132.82	0.239			VA05044876	0.46
6	1	1.25	6.0	20	45						5.0											B291589	132.36	132.82	0.136	PD/CA		VA05044876	0.46
																						B291590	STANDARD 2B		3.260	2B		VA05044876	
4	1	3.00	3.75	30	40						0.1		0.1									B291591	132.82	133.85	0.163			VA05044876	1.03
4	1	1.00	2.0	30	35						0.1		0.1									B291592	133.85	135.64	0.020			VA05044876	1.79
4	1	1.00	2.5	40							0.1		0.1									B291593	135.64	137.16	0.349			VA05044876	1.52
2	1	1.50	2.0	30	35						0.1		1.0									B291594	137.16	138.68	0.045			VA05044876	1.52
2	1	1.00	2.0	40							0.1		0.1									B291595	138.68	140.21	0.210			VA05044876	1.53
																						B291596	BLANK		<0.005			VA05044876	
7	1	0.75	2.5	40	30						0.1											B291597	140.21	141.73	0.027			VA05044876	1.52
																						B291598	141.73	142.95	0.012			VA05044876	1.22
																						B291599	142.95	144.49	0.023			VA05044876	1.54
3	1	0.50	1.0	40		0.1					0.1											B291600	144.49	146.30	0.014		sericite on selvages	VA05044876	1.81
2	1	0.75	1.5	30							0.1											B291601	146.30	147.83	0.009			VA05044876	1.53
2	1	0.75	1.5	30							0.1											B291602	146.30	147.83	1.910	DUP		VA05044876	1.53
						0.1		1														B291603	147.83	148.38	0.041			VA05044876	0.55
																						B291604	148.38	149.35	0.018			VA05044876	0.97
4	1	1.00	2.0	40	50						0.1		0.1									B291605	149.35	150.88	0.285			VA05044876	1.53
4	1	0.75	2.5	30							0.1											B291606	150.88	152.40	0.165			VA05044876	1.52
8	1	1.00	8.0	30	35						1.0		0.1									B291607	152.40	153.92	0.068			VA05044876	1.52
4	1	2.50	4.0	25	40						0.1											B291608	153.92	155.45	0.015			VA05044876	1.53
4	1	2.50	4.0	25	40						0.1											B291609	153.92	155.45	0.012	PD/CA		VA05044876	1.53
																						B291610	STANDARD 5E		1.35	5E		VA05046431	
4	1	3.00	3.75	25	45	0.1		1			0.1											B291611	155.45	156.97	0.047			VA05046431	1.52
4	1	0.50	1.0	15	40						0.1		0.1									B291612	156.97	158.50	0.04			VA05046431	1.53
						0.1		1					0.1									B291613	158.50	160.02	0.046			VA05046431	1.52
1	1	3.00	3.0	35							0.1											B291614	160.02	161.26	0.01			VA05046431	1.24
10	1	3.75	22.5	35	40						2.0											B291615	161.26	163.07	0.31			VA05046431	1.81
																						B291616	BLANK		<0.005			VA05046431	
6	1	1.25	3.5	35	40						1.0											B291617	163.07	164.59	0.159			VA05046431	1.52
1	6	0.50	0.5	30					0	5.0		20.0	2.0					3.0				B291618	164.59	165.60	0.077		selvage all altered - cannot distinguish	VA05046431	1.01
2	1	1.20	1.8	40	135					10.0			2.0																
3	1	1.00	2.5	35	50	8.0	chl/s/q	5		8.0	10.0	5.0	0.1									B291619	165.60	166.86	0.06			VA05046431	1.26
1	1	14.00	14.0	45		14.0	chl/s/cb	4	0	5.0	4.0	0.1						2.0				B291620	166.86	167.14	0.46		no alteration of 'rock' b/c sample is qtz vein w/selvage	VA05046431	0.28
2	1	0.60	1.0	45	25	1.5	chl/s	4	0		10.0		0.1									B291621	167.14	168.22	0.015			VA05046431	1.08
2	1	0.60	1.0	45	25	1.5	chl/s	4	0		10.0		0.1									B291622	167.14	168.22	0.011	DUP		VA05046431	1.08
1	1	1.50	1.5	30		1.0	chl/s	3		3.0								3.0				B291623	168.22	170.96	0.049			VA05046431	2.74
1	3	0.40	0.4	40	20	20.0	chl/s/cb	5		0.1																			
1	1	1.00	1.0	55		2.0	chl/s/q	4	0		15.0																margins abrupt		
1	1	1.50	1.5	25		4.0	chl/s/q	4			0.1		1.0														margins silicified		
2	6	1.00	2.0	25	30	10.0	chl	5			1.0		5.0				15										chalcocite?		
0																						B291624	170.96	172.56	0.025		no veins visible	VA05046431	1.60
3	1	1.50	3.5	150	40	0.5	chl/s	2	0		0.1		0.1									B291625	172.56	173.74	0.019			VA05046431	1.18
1	1	0.80	0.8	50		1.0	chl/s	1	0	0.0												B291626	173.74	175.26	0.043			VA05046431	1.52

DRILL LOG LEGEND - P1				DATE: June 1 - 4, 2005 PAGE 7 of 8							
DRILL HOLE # : DG05-278C				FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered			Carbonate 0 = No Effervescence 5 = Strong Effervescence			
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93											
	GEOLOGICAL DESCRIPTION						ROCK (Alteration)					
UNIT CODE	From → To:	From:	To:	Comments:			Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		173.74	175.26	Highly alt'd GND. 30-60% weathered out to clay minerals. Matrix material totally alt'd, so only large qtz and mafics left of GND. Clay vein at 20° to CA shows slickensides at ~80° to CA. Fractures at 50° continue; fract faces have				3	2	2	1	
10		175.26	176.78	Highly alt'd GND. 60% gone to clay minerals and sericite. One fracture face (to 15°) is light grey clay.			1	3	2	2	1	
10		176.78	178.31	Uneven fracture set at ~90° to CA. Highly alt'd GND cont'd. Qtz vein offset approx. 3cm, sinistral. (figures on original log sheet)			1	3	3	2	1	
10		178.31	179.83	Gradation over 30cm to very minor alt'n in the GND. First 30cm more silicified w/ grey qtz. One massive sulphide veinlet at 178.92m. Microfractures, randomly oriented, are infilled with calcite.				3		1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY:T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL:														Interval						
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
2	1	3.00	4.0	65			chl/s/q	3	1	0.0												B291627	175.26	176.78	**0.062**		selvage gone to alt'n	VA05046431	1.52
1	1	3.00	3.0	85		8.0	chl/s	3	1		2.0		1.0						3.0			B291628	176.78	178.31	**0.031**			VA05046431	1.53
1	1	3.00	3.0	85		8.0	chl/s	3	1		2.0		1.0						3.0			B291629	176.78	178.31	**0.03**	PD/CA		VA05046431	1.53
																						B291630	STANDARD 7G		**4.34**	7G		VA05046431	
1	6	0.30	0.3	35		1.5	q/chl	4		10.0	20.0							5.0				B291631	178.31	179.83	**0.024**			VA05046431	1.52
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-279C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1024m

BEARING: 000 | DIP: -50°

DATE STARTED: June 4, 2005 (night) | DATE COMPLETED: June 8, 2005 (day)

COORD SYSTEM: NAD 27: EASTING: 459701 NORTHING: 7099261

COORD SYSTEM: NAD 83: EASTING: 459586 NORTHING: 7099443

NAD 27 (CORRECTED for historic grid): EASTING: 459671 NORTHING: 7099271

SECTION LINE (historic grid): 459671E

LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 9.14

Deviation:

Casing: 9.14m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
9.14m	201.17m	GND

FROM	TO	ALTERATION
15	35	ox, ser, chl, arg, carb
55	65	ox, ser, chl, arg, carb
95	112	ox, ser, chl, arg, carb
135	175	ox, ser, chl, arg, carb
185	190	ox, ser, chl, arg, carb

FROM	TO	MINERALIZATION (Veins)
10	30	py, aspy, minor po
94	125	py, po, asy, v.minor cpy
134	160	py, po, aspy
168	201	py, aspy, po, v.minor cpy

SAMPLING DETAILS

Sample Sequence: B291632 to B291823

Requisition #: MASP448STRGOL.05Q | Date Shipped: 10-June-05

Lab Record #: VA05046971 | Date Received: 16-June-05

Duplicates:	B291642, B291662, B291682, B291702, B291722, B291742, B291762, B291782, B291802, B291822
Preparation Duplicate/ Check Assay:	B291649, B291669, B291689, B291709, B291729, B291749, B291769, B291789, B291809
Standards:	B291650(4D), B291670(1A), B291690(4D), B291710(7G), B291730(1A), B291750(4D), B291770(3C), B291790(4D), B291810(2B)
Blanks:	B291656, B291676, B291696, B291716, B291736, B291756, B291776, B291796, B291816

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+ 27 Corr)
50	335	49	001	002
100	334.3	49.2	000.3	001.3
200	334.8	48.4	000.8	001.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: June 4 - 8, 2005 PAGE 1 of 12	
DRILL HOLE # : DG05-279C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQB = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-9.14m			CASING (no recovery)						
10	9.14-201.17	9.14	15.24	V. broken and heavily oxidized GND. Alteration from minor to moderate. Veinlets grey qtz. V. poor recovery from 12.19 to 13.72m (19%). Rock is pebble-cobble size.	4	2				
10		15.24	18.29	Mod. to highly alt'd GND. One qtz vein has bands of alternating siderite and qtz. Adjacent to this is a zone of dark grey-black, grainy alt'n (old xeno?), ~6x4cm.	4	1			1	
10		18.29	24.38	Mod to highly alt'd GND. V. broken core: max 10cm long (1), most <5cm. From 21.34 to 24.38m recovery is poor (34% and 16%). Fewer small pebbles but core is still v. broken.	4	1			1	
10		24.38	25.91	V. broken core w/ one 20cm gouge zone, med. brown.	4	1		2		
10		25.91	27.43	Highly alt'd and broken core - one 10cm length. Colour pale brown.	4	2	1	1		
10		27.43	28.96	Highly to extremely alt'd GND.	4	2	1	1		
10		28.96	30.46	13% core recovery. Gouge to highly alt'd GND.	4	1		3		
10		30.46	32.00	Extremely alt'd to clay texture (90%), with qtz eyes and small GND pebbles	4	2		4	1	
10		32.00	33.56	Poor core recovery (14%). Pebbles.	4	1		2		
10		33.56	34.90	Extremely alt'd GND. Sand-sized, medium brown.	4			3	1	
10		34.90	36.40	Highly alt'd GND. Cobbles no bigger than 5cm. Veinlet at 34.05m w/ 1cm selvage (ox. 100%)	4	1		1	1	
10		36.40	39.37	Highly alt'd GND. Hematite oxidized near qtz veins (2mm subhedral grains).	4	1	1	2	1	
10		39.37	40.50	Highly alt'd GND. More competent, however, with pieces up to 15cm. Black ox'n product on uneven fracture faces. Limonite on microfractures. Gouge zone (5cm) between 2 competent, 6cm GND pieces. No slickensides.	5	2	1	1	1	
10		40.50	42.67	Extremely alt'd GND. Clay to sand-size (90%). Medium brown.	4	2	1	3	2	
10		42.67	43.76							
10		43.76	46.80	GND is v. broken and altered to gouge/sandy gravel with v. minor competent pieces. Core is v. limonite stained on fracs / pervasively and within clay yielding a rusty/yellow-brown color. Sulphides have undergone significant weathering (po + aspy). Qtz pieces in the core are visible indicating vning however thickness / amount and angle to CA are impossible to obtain. Sulphides are within veining or immediately adjacent.	4	2		2		
10		46.80	47.57							
10		47.57	48.90	GND becomes sandy, predominantly, w/ pieces of gravel and clay. Core is heavy limonite-stained and fracs are occasionally hematite-stained as thin skin on surface (black).	2	1		1		
10		48.90	49.03	Fault gouge with heavy limonite staining. Qtz vns w/ slickensides indicating fault movement, angle on surface is ~ 50° to CA.	3	1		2		
10		49.03	49.15							
10		49.15	50.01	At 49.15m is a 0.25cm wide oxidized pyrite vn, pure black, @~ 50° to CA.	5					
10		50.01	50.29	Fault gouge with a slickenside surface on contact at 35° to CA.	2	2		3		
10		50.29	50.41							
10		50.41	53.34	Core is altered to crumbly gouge w/ pervasive limonite and sericite. Core is v. soft yet recovery is good. Some vning can be seen but highly oxidized pyrite is interpretation.	2	4		2	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ca = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
1	0.5	1.0	25		2.0	q	3	2	5.0			5.0					5.0				B291632	9.14	10.67	0.297			VA05046971	1.53
1	1.0	3.0	40	10	0.5	q	3	2	5.0			5.0					5.0				B291633	10.67	12.19	0.175			VA05046971	1.52
																					B291634	12.19	13.72	0.227			VA05046971	1.53
1	1.0	2.5			1.0	q/s	3	3	0.1								5.0				B291635	13.80	15.24	0.083		pebbles of qtz (no angle avail.)	VA05046971	1.44
																					B291636	BLANK		<0.005			VA05046971	
1	3.0	5.0	50		1.0	q/cb	5	3	5.0			0.1					5.0				B291637	15.24	16.76	0.471			VA05046971	1.52
1	1.0	2.5	50		1.0	q	3	3	7.0			3.0					5.0	3.0			B291638	16.76	18.29	5.250		qtz on broken pieces	VA05046971	1.53
1	1.3	5.0	30		3.0	q/s	3	4	0.1			2.0					0.0	0.0			B291639	18.29	19.81	0.364			VA05046971	1.52
1	2.0	4.0	60					4				2.0					.	1.0			B291640	19.81	21.34	0.280		whole sample is altered - no selvage info	VA05046971	1.53
1	1.5	3.5	30		2.0	q	4	3	1.0			1.0						2.0			B291641	21.34	22.86	0.780			VA05046971	1.52
1	1.5	3.5	30		2.0	q	4	3	1.0			1.0						2.0			B291642	21.34	22.86	0.432	DUP		VA05046971	1.52
																					B291643	22.86	24.38	0.149			VA05046971	1.52
1	1.2	4.0	50		6.0	q	4	3	2.0			2.0					5.0				B291644	24.38	25.91	1.290			VA05046971	1.53
1	1.5	4.0	55	25	2.0	q/s	1	4				2.0									B291645	25.91	27.43	0.969			VA05046971	1.52
1	1.0	2.0	60	95	2.0	q	4	4	3.0			3.0					4.0				B291646	27.43	28.96	0.440			VA05046971	1.53
																					B291647	28.96	30.48	0.301			VA05046971	1.52
1	1.0	1.0	85																		B291648	30.48	32.00	1.030		whole sample is altered - no selvage info	VA05046971	1.52
1	1.0	1.0	85																		B291649	30.48	32.00	1.215	PD/CA		VA05046971	1.52
																					B291650	STANDARD 4D		0.416	4D		VA05046971	
1	1.0	1.0																			B291651	32.00	33.53	2.510		pebbles of qtz (no angle avail.). selvage altered	VA05046971	1.53
																					B291652	33.53	34.90	0.880			VA05046971	1.37
2	1.0	1.0	90														4.0				B291653	34.90	36.40	1.045		whole sample is altered - no selvage info	VA05046971	1.50
																					B291654	36.40	37.90	0.124			VA05046971	1.50
1	1.5	3.0	10		1.0	q	3	3	0.1								4.0				B291655	37.90	39.37	0.748			VA05046971	1.47
																					B291656	BLANK		<0.005			VA05046971	
1	0.5	0.5	65						0.1								4.0				B291657	39.37	40.50	0.109		qtz vein on small piece, not intersecting CA	VA05046971	1.13
1	0.5	0.5										0.1						4.0			B291658	40.50	41.20	0.325		can't see selvage	VA05046971	0.70
1	0.5	1.0							3.0			4.0					4.0	4.0			B291659	41.20	42.67	2.210		milky qtz on pebbles	VA05046971	1.47
1	0.5	2.0	50		0.1		2	2	0.1								4.0				B291660	42.67	44.20	0.383		2 qtz veins & qtz pieces	VA05046971	1.53
1	0.5	1.0	55	60																	B291661	44.20	45.72	0.359		2 qtz veins & qtz pieces	VA05046971	1.52
1	0.5	1.0	55	60																	B291662	44.20	45.72	0.263	DUP		VA05046971	1.52
1					0.1		1	1	0.1			0.1					4.0				B291663	45.72	47.24	0.618		1 qtz vein & qtz pieces	VA05046971	1.52
1			45	50					0.1			0.1									B291664	47.24	48.77	0.768		2 qtz veins & qtz pieces	VA05046971	1.53
1	1.25	3.0							0.1			1.0					4.0				B291665	48.77	50.29	0.499		KW noted up to 80% py in some veins	VA05046971	1.52
																					B291666	50.29	51.82	0.367			VA05046971	1.53
																					B291667	51.82	53.34	0.470			VA05046971	1.52

DRILL LOG LEGEND P1			DATE: June 4 - 8, 2005 PAGE 3 of 12								
DRILL HOLE # : DG05-279C			FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered			Carbonate 0 = No Effervescence 5 = Strong Effervescence				
Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQB = 85; QTZ = 90; FZ = 92; BZ = 93											
UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
10		53.34	54.86	Chloritized GND core, bleached, green-hued w/ little to no mafics. Minor calcite stringers (frac-filling mostly). Limonite on fracs, looks to be oxidized py on fracs.	2	2	2		1		
10		54.86	55.44								
10		55.44	55.84	Clay gouge alteration zone. Qtz eyes, looks like digested, rotten GND. Limonite abundant, making core / clay yellow-gold color.	2	1		4			
10		55.84	59.31								
10		59.31	59.91	Hydrothermal alteration zone, core becomes sandy to clay w/ some broken pieces. Heavy limonite staining. Qtz eyes present. Some red rusty bits (perhaps weathered sulphides).	3	1		2			
10		59.91	60.96	GND, same as previous unit	3	1		3	2		
10		60.96	64.01	Core has what looks to be a sheeted vn system. Veins are spaced ~ 5-10cm apart w/ similar core axis foliation of 45-50°. Minor dissem sulphides in vns.							
10		64.01	64.66	GND becomes etched and filled w/ limonite and sericite. Some bleaching through mafics. Intact core is easily broken w/ v. minor clay seems. Core is yellow-gold stained in color	3	2		1			
10		64.66	65.13	Large qtz vn. Some limonite and GND inclusive					1		
		65.13	66.78								
10		66.78	67.06	Gouge clay alteration seam, core reduced to sandy clay w/ small qtz eyes, heavy limonite staining. Qtz pieces indicating vning but too small to be certain.	2	1		4	1		
10		67.06	67.40								
10		67.40	67.78	Same GND as above, but w/ no qtz veining visible	2	1		4			
10		67.78	68.17								
10		68.17	69.15	GND becomes altered to bleached, sericite, grey-brown dull color. Minor green (chlorite hue) but not intense. Pervasive limonite, yet core is coherent. Abundant selvages w/ minor sulphides (aspy). Very little to no mafics, qtz vns visible @45-50° to CA, ~0.25-0.5cm thick, and continues to 96.68m.	3	1	2				
10		69.15	70.10								
10		70.10	72.23	Core is extremely broken to gravel and clay. Clay seams have reddish colours, possibly indicating py oxidation. Core is yellow-gold/rusty colour. Core has lost mafics in places, and has slight bleached/chloritic nature. Evidence of hydrothermal/faulting.	4	1	1	1			
10		72.23	75.38	GND is altered to a predominantly mafic-'free' state w/ only minor units of visible mafics. Core has a dull brown colour with visible sericite and minor chlorite. Some siderite w/in selvages. @74.34m pyrite vein oxidized to red/black and minor unoxidized crystals. Vein is ~0.75-1.5cm thick, at 50° to CA.	3	1	1				
10		75.38	76.02	Altered clay seam, hydrothermal alteration is evident from visible qtz eyes and some preserved gravel sized pieces of altered GND. Clay is yellow/gold and consistent in texture. No contacts preserved.	3			4			
10		76.02	77.50	Core remains altered as described in previous section (72.23-75.38m)	3	1	1.0				
10		77.50	83.82	Core remains altered as above description w/ what appears as a sheeted vein system. Veining/selvages are somewhat regular w/ spacing @5-20cm apart w/ a regular angle of 45-50° to CA.	2	1	1				
10		83.82	84.08	Clay seam at hydro alteration zone w/ a 5cm adjacent sulphide (aspy stringer) and veining zone. @84.08-84.13m, clay is gold yellow colour w/ qtz eyes	2	1		4			
10		84.08	89.37	Same as above unit, altered GND. description from 72.23-75.38m interval.	3	1	1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

PAGE 4 of 12

Selvage Alteration: ghf = chlorite, k = K-spar, s = sericite, q = quartz/silica, ab = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL													Interval						
					Selvages				Sulphides								Oxidation											
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)
1	0.25	0.25	55	60					0.1			0.1					4.0				B291668	53.34	54.86	**0.356**			VA05046971	1.52
1	0.25	0.25	55	60					0.1			0.1					4.0				B291669	53.34	54.86	**0.406**	PD/CA		VA05046971	1.52
																					B291670	ANDARD 1A		**0.754**	1A		VA05046971	
1	0.75	2.0	45	50					0.1								5.0				B291671	54.86	56.39	**0.135**			VA05046971	1.53
1	1.0	1.0							0.1								5.0				B291672	56.39	57.91	**0.156**		1 qtz vein & qtz pieces	VA05046971	1.52
1	0.25	2.75	15	45								0.1					1.0				B291673	57.91	59.44	**0.191**			VA05046971	1.53
1	2.25	3.0	55		0.1		2		0.1								4.0				B291674	59.44	60.96	**2.300**		2 veins plus pieces	VA05046971	1.52
1	1.0	3.0	45	50	0.1		1		0.1	0.1							2.0				B291675	60.96	62.48	**1.055**			VA05046971	1.52
																					B291676	BLANK		**<0.005**			VA05046971	
1	1.0	4.0	45	50	0.1		2					0.1					3.0				B291677	62.48	64.01	**2.280**			VA05046971	1.53
1	46.5	46.5	75		0.1		2					0.1					4.0				B291678	64.01	65.53	**0.279**			VA05046971	1.52
																					B291679	65.53	67.06	**0.071**		Qtz pieces	VA05046971	1.53
																					B291680	67.06	67.85	**0.103**		Qtz pieces	VA05046971	0.79
1	1.25	3.0	45		0.1		1		0.1			0.1									B291681	67.85	70.10	**0.261**			VA05046971	2.25
1	1.25	3.0	45		0.1		1		0.1			0.1									B291682	67.85	70.10	**0.071**	DUP		VA05046971	2.25
																					B291683	70.10	71.63	**0.250**			VA05046971	1.53
1	0.25	0.25	30		0.1		1	2									2.0				B291684	71.63	73.15	**0.177**			VA05046971	1.52
1	0.75	1.5	35	50	0.1			1	0.0								3.0				B291685	73.15	74.68	**0.138**			VA05046971	1.53
6	0.75	1.5	35	50	0.1			1	100.0								3.0									7' includes qtz AND sulph veins		
1	1.75	4.0	70	45	0.1		1	1													B291686	74.68	75.38	**0.804**			VA05046971	0.70
																					B291687	75.38	76.02	**0.168**			VA05046971	0.64
1	0.75	1.25	40	50	0.2		1	2	2.0												B291688	76.02	76.20	**0.323**			VA05046971	0.18
1	0.75	1.25	40	50	0.2		1	2	2.0												B291689	76.02	76.20	**0.315**	PD/CA		VA05046971	0.18
																					B291690	STANDARD 4D		**0.417**	4D		VA05046971	
1	1.25	4.25	60		0.1		1	2	1.0								2.0				B291691	76.20	77.72	**0.530**			VA05046971	1.52
	2.0	5.5	50	60					1.0								2.0				B291692	77.72	79.25	**0.424**		4 veins and other pieces	VA05046971	1.53
1	1.5	5.75	45		0.1		2		0.1								2.0				B291693	79.25	80.77	**0.378**			VA05046971	1.52
1	1.5	1.0	45	50					1.0			5.0					2.0				B291694	80.77	82.30	**1.235**		max sulph percents	VA05046971	1.53
1	1.5	5.0	50	45	0.1		1					1.0					2.0				B291695	82.30	83.82	**0.506**			VA05046971	1.52
																					B291696	BLANK		**<0.005**			VA05046971	
1	1.25	5.0	35	45					0.1			0.1					2.0				B291697	83.82	85.34	**0.510**			VA05046971	1.52

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005 PAGE 5 of 12		
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; M9ED = 80; HFLB = 81; PHYL = 82; BQB = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION			ROCK (Alteration)					
		From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		89.37	89.92	Clay seam w/ abundant qtz vn pieces with disseminations of aspy (trace).	2	2	1	3		
10		89.92	90.17							
10		90.17	90.48	Yellow-gold gouge w/ qtz eyes. Clay is relatively uniform; some minor pieces of altered GND. No visible sulphides. Inconclusive contact at 90.48m is preserved, @30-35° to CA.	2	1		3		
10		90.48	90.72							
10		90.72	90.80	Same gouge GND - description above	2	1		3		
10		90.80	91.32							
10		91.32	91.40	Same gouge GND - description above	2	1		3		
10		91.40	92.67							
10		92.67	92.80	Core becomes v. altered with dissems / vnlets of py and aspy (~2-5%). Somewhat oxidized at the contact @ 92.80m @ 60° to CA.	3	1				
10		92.80	93.13	Yellow to reddish-gold clay seam w/ GND rubble + qtz eyes. At 90.07m, a 1cm thick qtz vn @50-55° to CA (trace dissem py). At 93.13m, contact angle is 35° to CA.	3	1		5		
10		93.13	93.38	Core is v. decomposed but not to clay as yet. Qtz eyes are visible, core is soft but original altered brown core is still easily transparent. 93.38m: contact @~35° to CA, with some slickensides observed on adjacent GND. At 93.41, 93.53, and ~93.70m, 1-3cm thick qtz vns with py and aspy. Special Note: 68.17 to 96.68m, GND is of the same altered type best described in section: 72.23-75.38m	4	1		1		
10		93.38	94.80	Zone of high to extreme alt'n. One block competent core at 93.29 to 93.67m, with 2 qtz veins. Rest of sample is gouge/extremely alt'd to clay texture w/ alignment of sericite/chlorite @~90° to CA. Colour from bluish green to light yellowish brown. 3rd qtz vein has been folded w/in competent alt'n zone.	5	4	3	2		
10		94.80	95.75	Highly alt'd but competent core. V. broken. Colour med. brown.	4	2	1	1		
10		95.75	96.01	Strong slickensides along qtz vein margin. Tourmaline (?striated, v. hard, transparent to translucent, colourless to brownish black), + qtz + sericite: fault zone. Sample is one qtz vein; broken up.						
10		96.01	97.54	Strong to moderate alt'n. 2 large qtz veins in first 30cm. Fault gouge at 96.30m for ~10cm w/ 80% sericite, aligned. Qtz vein offset (brittle), on fracture @35° to CA. Slickensides aligned with long axis.	3	3	1	1	1	
10		97.54	98.52	Mod'ly alt'd GND. Limonite on microfractures is pervasive. Xeno at 98.8m: fine-grained diorite.	3	1			1	
10		98.54	99.06	Highly alt'd zone. Competent core w/ regular fractures to 50°. Med brown. Almost no GND texture left (just rounded qtz grains).	3		1			
10		99.06	100.58	Mod'ly alt'd GND with two vein sets. High angle offsets low angle.	2	1				
10		100.58	102.11	Mod'ly alt'd GND. Regular fracture set (6) to 45° and 135°. One has fault gouge material (clay) w/ slickensides. Also slickensides noted on low angle fractures.	3	1		1	1	
10		102.11	103.30	V. broken core. Fracture sets @45°/135° and low angle (0-15°). Gouge material in two low angle fractures. No slickens obvious but calcite smeared out.	3	2	1	1	1	
10		103.30	104.81	Minor to moderate alteration - slow gradation through sample, due to increasing number of veins and veinlets (selvages account for alteration)	3	1	2			
10		104.81	106.97	Mod'ly alt'd GND, w/ >2cm qtz veins @45°. Limonite on irregular fractures. At 105.86m, 2cm fault gouge-clay shows slickensides. Colour brownish grey.	3	1	1	2	1	
10		106.97	107.90	High to extreme alt'n. Limonite and calcite up to 1cm wide. Colour medium to pale yellowish brown. Boundary to less alt'd GND (grey, coarse texture) is at 30° to CA. Patches of orange rust (siderite?) speckle qtz vein and surrounding rock (20cm).	4	2	2	2	1	
10		107.90	109.33	Minor alt'n around veins and veinlets. Two noticeable xenoliths at 108.9m and 109.3m	1	1				
10		109.33	120.40	Minor alt'd GND w/ qtz veins. Regular breaking at 45° and 135°. Calcite on fract faces (<1mm thick). Diss aspy near fract w/in unalt'd GND. At 116.43m rock fract at 50° to CA (3) and some clay alt'n occurred (5cm wide).	1					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL													Interval						
					Selvages				Sulphides									Oxidation										
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)
6	1.25	5.0	35	45					0.1			0.1					2.0									5' includes qtz AND sulph veins		
1	0.5	0.5	20		0.1		1					0.1									B291698	85.34	86.87	**0.198**			VA05046971	1.53
1	0.75	1.25	20	30	0.1		1		0.1			0.1					2.0				B291699	86.87	88.39	**0.278**			VA05046971	1.52
																					B291700	88.39	89.37	**0.510**			VA05046971	0.98
												0.1									B291701	89.37	89.92	**0.447**		Qtz pieces w/ clay	VA05046971	0.55
												0.1									B291702	89.37	89.92	**0.915**	DUP		VA05046971	0.55
																					B291703	89.92	90.60	**0.110**		broken core	VA05046971	0.68
																					B291704	90.60	91.44	**0.117**		broken core	VA05046971	0.84
																					B291705	91.44	92.68	**0.098**			VA05046971	1.24
1	0.75	0.75	50						0.1			0.1									B291706	92.68	93.38	**2.970**			VA05046971	0.70
1	2.0	4.0	40	10				4	10.0			10.0					5.0	2.0			B291707	93.38	94.23	**2.750**		selvage alt'd out	VA05046971	0.85
																					B291708	94.23	94.80	**1.390**			VA05046971	0.57
																					B291709	94.23	94.80	**1.495**	PD/CA		VA05046971	0.57
																					B291710	STANDARD 7G		**4.430**	7G		VA05046971	
1	2.0	2.0	35					4	2.0								5.0				B291711	94.80	95.75	**0.564**		selvage alt'd out	VA05046971	0.95
1	20.0																				B291712	95.75	96.01	**9.690**		no angles b/c qtz is all broken up. selvage in alt. zone	VA05046971	0.26
1	3.0	7.0	45	35				4				0.1						2.0			B291713	96.01	97.54	**0.837**		selvage alt'd out	VA05046971	1.53
6	0.5	0.5	30		1.0	q/s	4	2	30.0			5.0					4.0	3.0			B291714	97.54	98.52	**0.587**			VA05046971	0.98
1	0.3	0.3	45		1.0	q	3	2				1.0																
																					B291715	98.52	99.06	**0.226**			VA05046971	0.54
																					B291716	BLANK		**<0.005**			VA05046971	
1	1.0	4.5	70		6.0	q	5	4	5.0			10.0					5.0	4.0			B291717	99.06	100.58	**0.857**			VA05046971	1.52
1	1.0	3.0	25	15	1.0	q			3.0			5.0					5.0	2.0										
1	1.0	1.0	45		0.0				0.1								5.0				B291718	100.58	102.11	**1.100**			VA05046971	1.53
1	0.4	0.8	30	45	1.5	q	2	3	5.0			10.0					5.0	1.0			B291719	102.11	103.30	**1.015**			VA05046971	1.19
1	2.0	7.5	30	45	2.0	q/s	4	1	5.0	5.0		10.0					3.0				B291720	103.30	104.80	**0.527**			VA05046971	1.50
1	3.0	3.0	45		5.0	qcwk	13	1	2.0			0.1					4.0				B291721	104.80	105.82	**1.325**			VA05046971	1.02
1	3.0	3.0	45		5.0	qcwk	13	1	2.0			0.1					4.0				B291722	104.80	105.82	**0.816**	DUP		VA05046971	1.02
1	3.0	4.5	45									0.1						1.0			B291723	105.82	106.48	**1.615**		selvage alt'd out	VA05046971	0.66
																					B291724	106.48	106.97	**0.387**			VA05046971	0.49
1	0.3	0.3	45									0.1						1.0			B291725	106.97	107.90	**0.321**		selvage alt'd out	VA05046971	0.93
1	2.0	7.0	45	30	1.0	q/s	3	3	3.0			5.0					2.0	1.0			B291726	107.90	109.33	**1.425**			VA05046971	1.43
1	4.0	9.0	45		1.0	chl/q	3	2		10.0		8.0									B291727	109.33	110.29	**2.920**			VA05046971	0.96

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005 PAGE 7 of 12		
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION			ROCK (Alteration)					
		From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		120.40	121.92	V. minor alt'n where qtz veins have dissipated into silicified zones (no clear vein boundaries) at 45° to CA w/ sulphides - included in the vein count, page 2.		1	1			
10		121.92	124.81	Qtz/aspy vein @ 45° to CA; 0.5cm. Aspy ~5-8%. GND adjacent on either side is bleached for ~3cm on either contact removing almost all mafics.	1					
10		124.81	130.03	AT 124.81m, a qtz/carb/sulphide aspy vein, @ 45-50°; width ranges from 0.5-0.75cm. Aspy is ~5% of vein components. No bleaching/alteration adjacent to vein	1	1			2	
10		130.03	130.50	Two 1cm qtz veins w/ 5cm chloritized margins.	2	1	2			
10		130.50	131.20	Chloritized/altered GND. Pervasively intruded w/ carbonate/qtz veining and sulphides (including ~1-10% py and ~5-15% aspy). Mafics are scarce in core. Core has a predominant grey colour. Zone ends w/ a slickensided surface @ 131.02m, 40° to CA.	2	1	1		2	
10		131.20	134.11							
10		134.11	135.64	GND altered throughout with calcite to crumbly texture. Approximately half the qtz veins are heavily silicified such that original vein is no longer seen as such, but more of a linear qtz-rich zone at the same angle as the real veins	1	1	1	1	3	
10		135.64	136.70	Minor alt'd. GND w/ pervasive veinlets of calcite overprinted by qtz veins.	1	2	1	1	2	
10		136.70	140.21	Highly alt'd GND. Colour is whitish green, only rounded patches of qtz grains remaining of original texture of GND. Qtz veins still visible as well but selvage is altered into main zone.	2	2	3	1	1	
10		140.21	140.61	Large qtz vein (23cm of core). Relatively low sulphide content						
10		140.61	142.04	GND as at 134.11m. Broken and calcitized.	1	2	1	1	3	
10		142.04	142.53	Less calcite zone w/ 4 large qtz veins. One xeno: fine-grained diorite, long axis parallel to nearby vein (4x2cm)		1	1		1	
10		142.53	143.26	GND as at 134.11m. Broken and calcitized		1	1		1	
10		143.26	145.56	More competent core; v. little calcite		1	1			
10		145.56	146.67	GND as at 134.11m; 50% broken and calcitic	1	2	2		1	
10		146.67	147.15	V. large qtz vein (37cm of core is 'pure' qtz); milky veinlets of calcite are incorporated.					1	
10		147.15	151.54	GND as at 134.11m; 50% broken and calcitic	1	2	1		2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL								Sulphides				Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other										
																						From	To						
3	0.5	0.5	45		1.0	cb/q	4	3	2.0			2.0					4.0	3.0											0.00
1	2.5	5.5	45		0.5	q/chl	2	2		10.0		5.0					2.0	1.0			B291728	110.29	111.56	0.163			VA05046971	1.27
1	2.5	5.5	45		0.5	q/chl	2	2		10.0		5.0					2.0	1.0			B291729	110.29	111.56	0.307	PD/CA		VA05046971	1.27
																					B291730	STANDARD 1A		0.987	1A		VA05046971	
1	2.5	4.0	45	25	1.0	q	2		1.0			5.0						4.0			B291731	111.56	112.78	0.244			VA05046971	1.22
1	1.0	1.0	45		0.0					2.0		1.0						5.0			B291732	112.78	114.30	0.024			VA05046971	1.52
1	1.5	4.0	45	55	0.5	q	2	0		5.0		1.0						2.0			B291733	114.30	115.82	0.265			VA05046971	1.52
1	2.0	5.0	45		2.0	q/s	3	1		5.0		2.0						3.0			B291734	115.82	117.35	0.428			VA05046971	1.53
1	2.5	6.0	45	25	4.0	q/chl	4	2		7.0		10.0						4.0			B291735	117.35	118.87	0.158			VA05046971	1.52
																					B291736	BLANK		<0.005			VA05046971	
1	2.5	8.0	45	15	4.0	q/chl	3	2	5.0	10.0	1.0	7.0					0.0	3.0			B291737	118.87	120.40	0.191			VA05046971	1.53
3	0.3	0.3	45		2.0	q/chl	4	1		2.0		1.0						4.0			B291738	120.40	121.98	0.148			VA05046971	1.58
1	1.0	7.0	45	55	1.0	q	3		2.0	8.0		5.0						3.0								silicified zones (old veins)		
1	0.75	2.0	45	30						0.1		7.0									B291739	121.92	123.44	0.160		max sulphide percents	VA05046971	1.52
1	1.00	5.25	45	50						0.1		5.0									B291740	123.44	124.97	0.127			VA05046971	1.53
1	1.25	5.5	45	50						0.1											B291741	124.97	126.49	0.289			VA05046971	1.52
1	1.25	5.5	45	50						0.1											B291742	124.97	126.49	2.070	DUP		VA05046971	1.52
1	0.25	1.0	50																		B291743	126.49	128.02	0.174			VA05046971	1.53
1	1.50	3.5	35	40						0.1											B291744	128.02	129.54	0.084			VA05046971	1.52
1	3.50	6.0	40	45						1.0		1.0									B291745	129.54	130.50	0.452			VA05046971	0.96
1	0.25								10.0			15.0									B291746	130.50	131.06	0.378		qtz pieces; max sulphide percentages	VA05046971	0.56
1	1.00	4.5	40	20						0.1											B291747	131.06	132.59	0.464			VA05046971	1.53
1	1.50	5.75	40	45						0.1		0.1									B291748	132.59	134.11	0.123			VA05046971	1.52
1	1.50	5.75	40	45						0.1		0.1									B291749	132.59	134.11	0.200	PD/CA		VA05046971	1.52
																					B291750	STANDARD 4D		0.416	4D		VA05046971	
1	1.50	8.0	45	60	2.0	q/chl	3	1		15.0	2.0										B291751	134.11	135.64	0.195			VA05046971	1.53
1	2.50	5.0	35	45	5.0	q/chl	5	1	10.0	10.0		10.0					2.0	1.0			B291752	135.64	136.70	0.640			VA05046971	1.06
1	4.00	5.0	40	25						5.0							3.0				B291753	136.70	138.26	0.271			VA05046971	1.56
3	0.50	1.0	35							2.0							3.0										VA05046971	
1	2.00	4.0	50						20.0			5.0					3.0				B291754	138.26	138.68	0.728			VA05046971	0.42
3	3.00	3.0	30			cb/chl			15.0			2.0					1.0	1.0									VA05046971	
1	1.00	4.0	50	30						10.0		3.0					1.0	1.0			B291755	138.68	140.21	0.240			VA05046971	1.53
																					B291756	BLANK		0.012			VA05046971	
1	23.00	23.0	40						5.0	3.0							3.0				B291757	140.21	140.61	0.044			VA05046971	0.40
1	5.00	9.0	45	55	3.0	q/chl	4	0		5.0		2.0						3.0			B291758	140.61	142.04	0.136			VA05046971	1.43
1	3.00	12.0	45	55	3.0	q/chl	4	0		10.0		5.0						3.0			B291759	142.04	142.53	0.169			VA05046971	0.49
1	1.00	1.0	55		1.0	q	1														B291760	142.53	143.26	0.298			VA05046971	0.73
1	2.00	11.0	40	75	3.0	q/chl	3	0		8.0		5.0						4.0			B291761	143.26	144.78	0.357			VA05046971	1.52
1	2.00	11.0	40	75	3.0	q/chl	3	0		8.0		5.0						4.0			B291762	143.26	144.78	0.238	DUP		VA05046971	1.52
1	2.00	6.0	45		4.0	q/chl	3	0		2.0	0.1										B291763	144.78	145.56	0.270			VA05046971	0.78
1	2.00	8.0	45	30	2.0	q/chl	3	0		10.0		2.0						3.0			B291764	145.56	146.67	0.491			VA05046971	1.11
1	37.00	37.0	60	140	0.0							5.0						3.0			B291765	146.67	147.15	0.139			VA05046971	0.48
1	1.00	3.0	60		3.0	q	4	0		5.0											B291766	147.15	148.30	1.090			VA05046971	1.15
1	1.00	2.5	60		2.0	q/chl	3	1		5.0		5.0						3.0			B291767	148.30	149.35	0.957			VA05046971	1.05
1	4.00	7.5	65	70	2.0	q/chl	2	1		4.0											B291768	149.35	150.88	0.201			VA05046971	1.53
1	4.00	7.5	65	70	2.0	q/chl	2	1		4.0											B291769	149.35	150.88	0.310	PD/CA		VA05046971	1.53
																					B291770	STANDARD 3C		0.081	3C		VA05046971	
1	2.00	6.0	60	50	1.0	q/chl	2	0		4.0											B291771	150.88	151.54	0.178			VA05046971	0.66

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005	PAGE 9 of 12		
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BOAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION			ROCK (Alteration)					
		From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		151.54	153.04	Sheeted vein system w/in calcitic GND.	1	2	1		2	
10		153.04	153.77	More sheeted veins, slightly more rust on microfractures at 30° to CA	2	2	1		1	
10		153.77	154.70	Highly alt'd section (chl) follows 1cm qtz vein (included in last sample). GND texture erased to whitish green homogeneous rock. Veinlets (0.1cm) of pure pyrite. Fractured on one to shiny plate w/ black ox'n product on surface (wipes away easily).	1	3	4		1	
10		154.70	155.45	Minor alt'd GND hits alt'd section from above at 80° to CA. Qtz veins silicified so appears as all selvage		1	2		1	
10		155.45	156.48	Minor alt'd GND. Calcite veinlets pervade and weaken rock, generally at 30°-50°.		1	1	1	2	
10		156.48	159.56	Minor to mod'ly alt'd GND (selvages produce mod alt'n). Calcite vnlets still pervasive & cause breakage generally at 40-60° to CA.	1	2	2		2	
10		159.56	160.57	Carb & sericite alt'd GND. Color is light grey, texture alt'd to more planar (pseudo-foliation), defined by tabular sericite & calcite. One fracture (to 20°) has smeared out pyrite (gold, platey, striated) at 20° to CA w/ calcite/sericite elongate to 25° from the other side (2 episodes movement?). Sample <1% py.		3			3	
10		160.57	161.54	Limonite appears on frac faces, at 20° & 45° to CA; still v. broken.	1	3			2	
10		161.54	163.07	Limonite increases w/in carb/ser alt'd rock so very crumbly. Color is light grey w/ rust-brown along fracs.	2	3			2	
10		163.07	164.59	Cont'd limonite as irregular fracs every few cm to 163.84m. After this, fewer limonized fractures, but calcite still present on them. Xeno 3x2cm f-grained (and foliated) diorite.	1	3			2	
10		164.59	166.12	V. minor alt'n in qtz-rich GND. Diss po & py throughout sample (<2%). Regular fractures @ 50°, lim no longer. 2x1cm xeno 3cm from qtz vn.		3			2	
10		166.12	167.64	Carb/sericite still present along numerous veinlets in random & irregular fractures.		3			2	
10		167.64	169.16	Minor alt'd GND. Two gouge sections @167.85m (4cm) & 168.21m (1.5cm). Alt'd to clay/sand size; no notable slickensides.	1	3		1	2	
10		169.16	171.40	V. minor alt'd GND. Only alt'n is w/in selvages of numerous qtz vns.	1	2	1		2	
10		171.40	172.26	Large qtz vn w/ lenses of massive sulphides. Selvage from 171.4-171.55m. Vein from 171.55-171.87m, selvage from 171.87-172.00m. Vein (3cm) after that w/ 3cm selvage.						
10		172.26	172.78	Alt'd GND w/ 4 veins of massive sulphides.	1	3	3	1	1	
10		172.78	173.62	Mod'ly alt'd GND		2	2		1	
10		173.62	174.29	Mod-highly alt'd GND. Selvages dominate the sample.		3	3			
10		174.29	175.06	Highly alt'd GND. Competent core. Color whitish green to pale grey.		3	3		1	
10		175.06	175.66	Carb/qtz alt'd GND. Crumbly texture, white to light grey in color.						
10		175.66	175.91	Gouge zone. Clay to gravel sized pieces of GND.						
10		175.91	176.15	Chloritized zone w/ 4 qtz veins. Massive pyrite forms in 0.5cm wide lenses adjacent to qtz; Rock effervesces in acid along these lenses - siderite (oxidized pyrite + carbonates)						
10		176.15	177.76	Unaltered GND						
10		177.76	184.40	Alt'd selvages around numerous qtz veins make up bulk of section.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL													Interval						
					Selvages				Sulphides									Oxidation										
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)
1	5.00	26.0	50		3.0	q/chl	4	1	15.0	10.0		1.0					4.0	4.0			B291772	151.54	153.04	**0.163**			VA05046971	1.50
1	2.50	10.0	60		1.0	q/chl	2	1	5.0	3.0							4.0				B291773	153.04	153.77	**0.456**			VA05046971	0.73
1	0.50	0.5	80						2.0		1.0						4.0				B291774	153.77	154.70	**0.239**			VA05046971	0.93
6	0.10	0.1	50						100.0								4.0											
1	0.50	2.0	50	80	3.0	chl/q	3	0	2.0	5.0	1.0	7.0					1.0				B291775	154.70	155.45	**0.829**			VA05046971	0.75
																					B291776	BLANK		**<0.005**			VA05046971	
1	2.00	3.0	40		2.0	q/chl	3	0	7.0			2.0					3.0	1.0			B291777	155.45	156.48	**0.292**			VA05046971	1.03
1	3.00	8.5	50	70	4.0	chl/q	4	0		10.0	1.0	5.0									B291778	156.48	157.79	**0.376**			VA05046971	1.31
1	1.20	5.0	50	40	3.0	q/chl	4	0		5.0											B291779	157.79	159.56	**0.166**			VA05046971	1.77
																					B291780	159.56	160.57	**0.321**			VA05046971	1.01
1	1.0	2.0	30	40	1.0	q/s	4	0		5.0											B291781	160.57	161.54	**0.749**			VA05046971	0.97
1	1.0	2.0	30	40	1.0	q/s	4	0		5.0											B291782	160.57	161.54	**0.395**	DUP		VA05046971	0.97
1	1.5	2.0	30	80	1.0	q/s	3	1		5.0											B291783	161.54	163.07	**1.105**			VA05046971	1.53
1	1.5	2.5	45	55	1.0	q/s/cb	2	1		8.0	0.1										B291784	163.07	164.59	**0.204**			VA05046971	1.52
1	1.5	3.0	60	45	2.0	q/s	4	0		10.0	1.0	5.0					1.0				B291785	164.59	166.12	**0.251**			VA05046971	1.53
1	1.0	3.0	45						0.1	5.0											B291786	166.12	167.64	**0.899**			VA05046971	1.52
1	1.0	5.0	55	45	2.0	q/s	4	1	3.0	8.0		1.0					5.0				B291787	167.64	169.16	**0.653**			VA05046971	1.52
1	2.0	7.0	55		1.0	q/s/cb	4	1	1.0	5.0		2.0					3.0				B291788	169.16	170.74	**0.191**			VA05046971	1.58
1	2.0	7.0	55		1.0	q/s/cb	4	1	1.0	5.0		2.0					3.0				B291789	169.16	170.74	**0.442**	PD/CA		VA05046971	1.58
																					B291790	STANDARD 4D		**0.368**	4D		VA05046971	
1	2.5	5.0	40	70	2.0	q/s/cb	4	1	2.0	8.0		5.0					3.0	3.0			B291791	170.74	171.40	**0.301**			VA05046971	0.66
1	32.0	32.0	60		30	q/s/cb	5	1	20.0	5.0		10.0					4.0	1.0			B291792	171.40	172.26	**7.760**			VA05046971	0.86
6	0.6	2.4	60						10.0			75.0					4.0	0.0			B291793	172.26	172.78	**9.370**		in alt'n zone - selvages not distinguishable	VA05046971	0.52
1	1.0	2.0	60																							adjacent to sulph veins		
1	1.0	4.0	70	130	10	q/s/cb	4	0	1.0	5.0		5.0									B291794	172.78	173.62	**0.169**			VA05046971	0.84
1	0.5	3.0	55		10	q/s/cb	5	0	6.0	10.0		4.0					3.0				B291795	173.62	174.29	**0.373**			VA05046971	0.67
																					B291796	BLANK		**0.030**			VA05046971	
1	1.0	1.0	55						0.1	5.0		0.1					4.0				B291797	174.29	175.06	**2.130**			VA05046971	0.77
1	0.8	1.6	60		1.0	q/s/cb	4	0	0.1	8.0											B291798	175.06	175.66	**0.136**			VA05046971	0.60
																					B291799	175.66	175.91	**0.473**			VA05046971	0.25
1	1.0	3.0	45		16.0	q/s/cb	5	0	15.0								3.0				B291800	175.91	176.15	**1.645**			VA05046971	0.24
1	1.0	5.0	45		10.0	chl	5	0	1.0	5.0											B291801	176.15	177.76	**0.393**			VA05046971	1.61
						s	5																					
						cb	2																					
1	1.0	5.0	45		10.0	chl	5	0	1.0	5.0											B291802	176.15	177.76	**0.562**	DUP		VA05046971	1.61
						s	5																					
						cb	2																					
1	20.0	20.0	45		50.0	chl	4		30.0								4.0				B291803	177.76	178.30	**0.868**			VA05046971	0.54
						s	4																					
						cb	4																					
1	1.0	2.0	45		1.0	q	3	0		3.0		1.0									B291804	178.30	179.83	**0.135**			VA05046971	1.53
						chl	2																					
3	0.5	0.5	20		1.0	cb	3	0	0.0												B291805	179.83	181.36	**0.280**			VA05046971	1.53
						q	3																					
1	1.0	4.0	45		0.5	q	2	0		12.0	1.0						2.0				B291806	181.36	182.88	**0.398**			VA05046971	1.52
1	1.0	3.2	50		7.0	q	5	0		5.0											B291807	182.88	184.40	**0.037**			VA05046971	1.52
						s	2																					
						chl	3																					

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005	PAGE 11 of 12	
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BCAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		185.93	186.83	Rounded xeno w/ ragged edges, 3x2cm, at 186.25m.						
10		186.83	188.07	Minor alt'd GND. V. broken up due to calcite and limonite pervading along microfractures and throughout matrix of GND.	1	3	1	1	1	
10		188.07	188.98	Minor alt'd GND. Lim & calcite on microfractues. Xenolith at 188.65m, 3x2cm.	1	2		1	1	
10		188.98	190.50	GND w/ calcite throughout matrix and microfractures. Very broken and crumbly core		2	1	2	2	
10		190.50	201.17	Unalt'd GND w/ qtz and qtz/carb veins. At 190.62, rounded xeno of fine-grained diorite w/ 2mm rxn rims. Ox'd py (90%) + aspy (10%) concentrated in 10cm zones: at 190.90m-191.00m and at 192.02-192.12m. No affiliated veinage. Xenoliths at: 194.5m, 195.4m, and 196.55m.		1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

PAGE 12 of 12

094876

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
					Selvages				Sulphides								Oxidation											
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	2.0	5.5	50		15.0	chl	4		10.0					10.0							B291808	184.40	185.93	0.166			VA05046971	1.53
						q	2																					
						s	3																					
3	2.0	5.5	50		15.0	chl	4		10.0					10.0							B291809	184.40	185.93	0.138	PD/CA		VA05046971	1.53
						q	2																					
						s	3																					
																					B291810	STANDARD 2B		3.020	2B		VA05046971	
1	2.0	2.0	50		10.0	chl	4		10.0	10.0																		
						q	3																					
						s	3																					
1	1.2	1.2	70		12.0	chl															B291811	185.93	186.83	0.107			VA05046971	0.90
						q																						
3	0.2	2.0	30	70	4.0	chl																						
						q																						
						s																						
1	1.0	1.0	45		1.0	q	2	0				1.0						5.0			B291812	186.83	188.07	0.057			VA05046971	1.24
						s	2																					
																					B291813	188.07	188.98	0.022			VA05046971	0.91
1	4.0	4.0			20.0	chl	4	0				5.0						4.0			B291814	188.98	190.50	4.490		angles not dist. b/c qtz in pieces.	VA05046971	1.52
						s	4																					
1	0.5	0.5	50		0.2	q	2	0	0.0												B291815	190.50	192.02	0.063			VA05046971	1.52
																					B291816	BLANK		<0.005			VA05046971	
3	0.5	2.0	45		1.5	q	3	0	3.0	5.0		1.0					2.0	4.0			B291817	192.02	193.55	0.052			VA05046971	1.53
						chl	2																					
						cb	2																					
6	0.5	0.5	45		4.0	chl	4	3				10.0														nice, euhedral aspy, up to 1.3cm long			
1	0.5	1.0	60		1.5	chl	2	0	2.0	10.0							5.0				B291818	193.55	195.07	0.072			VA05046971	1.52
						q	3																					
1	1.5	5.0	45	60	1.0	q	3	0		8.0	1.0	5.0						3.0			B291819	195.07	196.60	0.857			VA05046971	1.53
						chl	2																					
1	2.0	5.0	45		2.0	q	3		5.0	3.0											B291820	196.60	198.12	0.414			VA05046971	1.52
						chl	1																					
1	2.0	8.0	45		0.5	q	1			3.0		1.0						2.0			B291821	198.12	199.64	3.380			VA05046971	1.52
1	2.0	8.0	45		0.5	q	1			3.0		1.0						2.0			B291822	198.12	199.64	1.130	DUP		VA05046971	1.52
1	1.5	11.0	45		0.5	q	2		2.0		1.0	8.0						0.0			B291823	199.64	201.17	0.208			VA05046971	1.53
																							EOH					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-280C

PROJECT: Dublin Gulch - 1735

DATE STARTED:	DATE COMPLETED:
06-Jun-05	10-Jun-05
LOGGED BY:	
Kristian Whitehead & Terry Croteau	
CONTRACTOR:	
Britton Brothers	

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 6.10m
Deviation:
Casing: 6.10m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

FROM	TO	LITHOLOGY
6.10	202.78	Granodiorite

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

GROUND ELEVATION:
BEARING: 000 | DIP: -50°
COORD SYSTEM: NAD 27: | EASTING: 459107 | NORTHING: 7099141
COORD SYSTEM: NAD 83: | EASTING: 458988 | NORTHING: 7099328
NAD 27 (CORRECTED for historic grid): | EASTING: 459077 | NORTHING: 7099151
SECTION LINE(historic grid)

SAMPLING DETAILS

Sample Sequence: B292501 - B292559
Requisition #: MASP448STRGOL.05Q | Date Shipped: 10-June-05
Lab Record #: VA05047189 | Date Received: 27-June-05
Sample Sequence: B292560 - B292707
Requisition #: MASP448STRGOL.05Q | Date Shipped: 13-June-05
Lab Record #: VA05047825 | Date Received: 30-June-05

Duplicates:	B292502, B292522, B292542, B292562, B292582, B292602, B292622, B292642, B292662, B292682, B292702
Preparation Duplicate/ Check Assay:	B292509, B292529, B292549, B292568, B292589, B292609, B292629, B292649, B292669, B292689
Standards:	B292510, B292530, B292550, B292570, B292590, B292610, B292630, B292650, B292670, B292690
Blanks:	B292516, B292536, B292556, B292576, B292596, B292616, B292636, B292656, B292676, B292696

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+27 Corr)
50	333.0	50.7	359.0	000.0
125	333.3	51.3	359.3	000.3
207	334.7	51.4	000.7	001.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005 PAGE 1 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-6.10			Overburden - Drill Casing; no recovery						
10	6.10-202.78			GND 40% qtz, 20% kspar, 15% bt, 10% Hal	3			1		
10		6.10	10.67	Broken GND: Core is extremely weathered and broken. Most pieces are angular, but some subangular - rounded. Sugary textured GND also present throughout. Lim is pervasive, and recovery is poor						
10		10.67	12.19	GND alterations trends to more clay rich gouge. Qtz eyes present with GND frags. Lim is pervasive.	3			2		
10		12.19	13.72	GND becomes slightly altered, lim is pervasive. @12.39m, GND becomes more fractured and sugary textured, lim staining becomes more intense. Veinlets present in fractured core; angles are indeterminate.	2			1		
10		13.72	14.02	Core is fractured and broken. Lim is pervasive. Clay alteration is less intense. Veinlets in section appear to be running at 35° to CA	2			1		
10		14.02	15.34							
10		15.34	16.50	Gouge, clay and sand w/ minor gravel pieces. Limonite is heavy on fracs. Zone of hydrothermal alteration. Limonite abruptly ends @ 16.90m	3	1		3		
10		16.50	16.76							
10		16.76	18.29	Core is extremely broken w/ poor core recovery. Aspy can be seen as thin coating on what looks like fractured surfaces	2					
10		18.29	19.29							
10		19.29	21.50	At ~19.20m: a fault/alteration zone. Evident from sandy and clay residue on core. Looks like aspy is remnant, but oxidized	2	1		1		
10		21.50	26.63	GND has bleached intervals, core has suffered some decay from sericite of fracs as evidence, broken core is demonstrating aspy oxidation and crystals	2	2	1	1	0	
10		26.63	31.37	Core becomes intensely oxidized to a dull brown colour, limonite is on fracs and moderately pervasive. Sericite is abundant on fracs and is pervasive. Chlorite is weak to moderate. Core is soft w/ oxidized aspy on fracture surfaces. Veins are essentially relict w/ oxidized aspy. Mafics are scarce and core crumbles when scratched in sections	4	3	2	1		
				From 28.63m to 28.60m, an orangey-gold coloured clay seam w/ oxidized aspy & possibly py. Contact @ 28.69m preserved @ 42° to C.A.	3	2		4		
				Another clay seam from 29.05 to 29.19m. Clay is uniform, light dull brown, w/ minor orangey-gold colours on contact. Uncertain if contact @ 29.19 is preserved but @ 35° to C.A.	3	2		5		
				Clay seam from 29.62 to 29.84m; core is orangey tiger colour. Oxidized and intact aspy and py	3	2		4		
				Clay seam from 30.48 to 30.91m; vein is relict by aspy veining, @~50°. Core is abundant w/ limonite	5	1	1	3	1	
10		31.37	31.50							
10		31.50	33.46	At 31.50m limonite completely and abruptly ends. GND is altered to a grey sericite rich, soft core. Mafics are still present, yet less in abundance than in unaltered GND. Sericite is pervasive and abundant on fracs and vein contacts. Qtz veins are somewhat intact w/ diss oxidized/unaltered aspy predominant. Core is essentially light grey in colour and uniform	4	4	1	2	1	
10		33.46	34.69							
10		34.69	35.08	Grey-white clay gouge alteration zone. No contacts preserved, some minor dissem ox'd aspy	4	3	1	4	1	
10		35.08	36.36							
10		36.36	38.95	At 36.36m, fault/slickensides @ 30° to CA, aspy/qtz vein, aspy ~25%, fault appeared to cut through vein, not activate along vein						
10		38.95	39.43	GND loses its mafics, core is dull greenish grey w/ sericite and chlorite present	3	2	2			
10		39.43	39.70	Semi massive aspy + py qtz vein. Sulphides are somewhat concentrated @ centre of vein w/ stringers/blebs running outwards. Py content ~3-5%, aspy ~40-45%. Qtz remainder w/ qtz being an opaque white						
10		39.70	40.49	GND is essentially digested to qtz eyes and sericite clay (good recovery). Core has a light green chlorite hue and has relict aspy and py vein/veinlets. 39.70 contact @ 30°, 40.49 contact has slicken lineations indicating a fault @ 40°	5	5	2	5		
10		40.49	40.63							
10		40.63	40.65	One 2.25cm thick qtz vein w/ disseminated aspy + py. angle 35-40°. Photo of area included.						
10		40.65	41.03							
10		41.03	43.54	GND continues to be devoid of mafics; sericite and chlorite to a minor state dominate, core is bleached with powdery, light grey colour.	3	3	1			
				From 42.14-42.35m, core is altered to white-grey clay and qtz eyes. Slickensided surface @~50° to CA. Surface had minor aspy 'slickened'.	3	4	1	4		
10		43.54	44.20	GND alteration zone, begins with clay predominant and then progresses to clay/ qtz eyes and broken core. All core is bleached with little to no mafics. Aspy is dissem w/ py. Sericite abundant on fracs and mod'ly pervasive	3	3	1	2		
10		44.20	46.50							
10		46.50	47.42	Hydrothermal alt'n zone (gouge). Sericite/qtz eyes/ grey-white clay w/ dissem aspy.	3	3		3		
10		47.42	48.15	Alt'd / bleached core as progressing from above. Gouge unit @47.85-47.93m. Sulphides (semi-massive) pyrite (30%), aspy (5-10%).	3	3	2	1		
10		48.15	50.09							
10		50.09	50.20	Clay gouge unit. Clay is light grey with aspy ox'd within (~5%)	3	3	1	5		
10		50.20	53.23							
10		53.23	53.38	Gouge, broken core, alteration zone. Core is light grey abundant w/ sericite, bleached	3	3	1	3	2	
10		55.38	55.59	Chlorite alteration zone. Core is light grey white w/ green hue. Sericite abundant	3	3	2			
10		55.59	56.39	Gouge/qtz eyes w/in semi-competent hydrothermal alteration zone. Core is light grey w/ pervasive sericite and on frac. Minor carbonates. Trace chlorite	3	3		2	1	
10		56.39	56.61	Medium grey uniform clay, looks like aspy clay. Directly adjacent @ 56.53-56.61m a qtz vein w/ aspy stringers	3			5		
10		56.61	57.09	Gouge alteration zone, core is white grey w/ minor green hue (chlorite). Qtz eyes, sericite dominant	3	4	1	4		

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To						
0																														
0																						B292501	6.10	7.62	0.088			VA05047189	1.52	
0																						B292502	6.10	7.62	0.062	DUP		VA05047189	1.52	
0																						B292503	7.62	9.14	0.102			VA05047189	1.52	
0																						B292504	9.14	10.67	0.143			VA05047189	1.53	
0																						B292505	10.67	12.19	0.199			VA05047189	1.52	
3	1	0.2	0.2										5.0									B292506	12.19	13.72	1.020		Veinlets are broken and difficult to orient	VA05047189	1.53	
1	1	0.2	0.2										3.0									B292507	13.72	14.02	0.332		Veinlets are broken and difficult to orient	VA05047189	0.30	
																						B292508	15.24	16.76	0.430			VA05047189	1.52	
																						B292509	15.24	16.76	0.509	PD/CA		VA05047189	1.52	
																						B292510	STANDARD 6F		2.650	6F		VA05047189		
1	1	0.75											0.1									B292511	16.76	18.29	0.122			VA05047189	1.53	
1	6	0.25	0.25	40									50.0									B292512	18.29	18.90	0.161			VA05047189	0.61	
										0.1	1.0											B292513	18.90	19.81	0.332			VA05047189	0.91	
1	1	0.25	0.25	30	35								1.0					1.0				B292514	19.81	21.34	0.276			VA05047189	1.53	
													3.0									B292515	21.34	22.86	0.145		QTZ PIECES; aspy tr to 3%	VA05047189	1.52	
																						B292516	BLANK		<0.005			VA05047189		
3	1	0.75	1.5	40	55								5.0									B292517	22.86	24.38	0.460		aspy: tr. to 5%	VA05047189	1.52	0.225
7	1	1.0	3.5	35	45	0.1	1						5.0									B292518	24.38	25.91	0.231		aspy: tr. to 5%	VA05047189	1.53	0.356
7	1	1.5	3.25	35	85								3.0									B292519	25.91	27.76	0.336		aspy: tr. to 3%	VA05047189	1.85	0.365
4	1	0.5	1.5	45						1.0			5.0									B292520	27.76	29.05	0.241		py: tr. to 1%; aspy: tr. to 5%	VA05047189	1.29	0.531
										1.0			3.0									B292521	29.05	30.48	0.208		py: tr. to 1%; aspy: tr. to 3%	VA05047189	1.43	0.471
										1.0			3.0									B292522	29.05	30.48	0.283	DUP	py: tr. to 1%; aspy: tr. to 3%	VA05047189	1.43	
										1.0			8.0					5.0				B292523	30.48	31.50	0.418			VA05047189	1.02	0.539
										0.1			10.0					5.0				B292524	31.50	32.00	0.503			VA05047189	0.50	
2	1	0.5	1.0	50	40					0.1			2.0					4.0				B292525	32.00	33.53	0.299			VA05047189	1.53	0.449
										0.1			0.1					4.0				B292526	33.53	34.69	0.483		pieces	VA05047189	1.16	0.601
													1.0									B292527	34.69	35.06	0.169		pieces	VA05047189	0.37	
2	1	0.25	0.5	45						0.1		5.0										B292528	35.06	36.58	0.263			VA05047189	1.52	0.685
2	1	0.25	0.5	45						0.1		5.0										B292529	35.06	36.58	0.261	PD/CA		VA05047189	1.52	
																						B292530	STANDARD 5E		1.250	5E		VA05047189		
13	1	1.0	8.5	45	75					1.0			25.0									B292531	36.58	38.10	0.267			VA05047189	1.52	0.372
4	1	0.75	2.25	50						0.1	0.1		15.0					1.0				B292532	38.10	39.43	0.191			VA05047189	1.33	0.35
1	1	11.0	11.0	45	50					5.0			45.0					2.0				B292533	39.43	39.70	0.249		includes sulph veins	VA05047189	0.27	0.371
										1.0			10.0					2.0				B292534	39.70	40.49	0.166		clay altered	VA05047189	0.79	
																						B292535	40.49	41.25	0.050			VA05047189	0.76	
																						B292536	BLANK		<0.005			VA05047189		
1	1	3.0	3.0	50		0.1	1						1.0									B292537	41.25	42.42	0.103			VA05047189	1.17	0.229
4	1	1.0	2.0	45		0.1	1						5.0									B292538	42.42	43.54	0.115			VA05047189	1.12	0.177
													5.0									B292539	43.54	44.20	0.167		qtz pieces	VA05047189	0.66	
4	1	0.75	2.25	55	50								1.0									B292540	44.20	45.72	0.162			VA05047189	1.52	0.334
2	1	0.5	1.0	55	60								3.0									B292541	45.72	46.95	0.096			VA05047189	1.23	
2	1	0.5	1.0	55	60								3.0									B292542	45.72	46.95	0.110	DUP		VA05047189	1.23	0.195
2	1	1.25	1.75	45									5.0									B292543	46.95	48.15	0.072		alteration zone	VA05047189	1.20	0.212
2	1	0.5	0.75	50									2.0									B292544	48.15	48.77	0.085			VA05047189	0.62	
1	1	0.25	0.5	30									2.0									B292545	48.77	50.21	0.062			VA05047189	1.44	0.243
4	1	1.0	1.75	40	55								2.0									B292546	50.21	51.82	0.049			VA05047189	1.61	0.252
2	1	0.25	0.5	50	60																	B292547	51.82	53.38	0.074			VA05047189	1.56	0.252
1	4	1.0	1.0	40									3.0					1.0				B292548	53.38	54.86	0.041			VA05047189	1.48	0.226
1	4	1.0	1.0	40									3.0					1.0				B292549	53.38	54.86	0.041	PD/CA		VA05047189	1.48	
																						B292550	STANDARD 2B		2.870	2B		VA05047189		
1	1	0.5	0.5	30									0.1									B292551	54.86	55.33	0.025			VA05047189	0.47	0.196
4	1	4.0	5.75	35	40					2.0			2.0									B292552	55.33	56.39	0.149			VA05047189	1.06	
1	1	4.5	4.5	40									3.0									B292553	56.39	57.91	0.128			VA05047189	1.52	0.214

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005 PAGE 3 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQB = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		57.09	57.91	Core continues to be bleached, devoid of mafics, sericite rich, yet competent area caught between 2 hydrothermal alt'n zones. Dissem aspy (1%) and py (tr.)	3	3		1		
10		57.91	58.91	Gouge alteration zone, core is white grey w/ minor green hue (chlorite). Qtz eyes, sericite dominant	3	3	1	3		
10		58.91	61.00	Core is altered/bleached, yet competent. Core is light grey w/ green (chl) hue. Core is easily scratched, little to no mafics. Sericite on fracs, and moderately pervasive	3	3	1	3.0		
10		61.00	61.32							
10		61.32	61.71	Core has been etched and bleached, however, mafics are still intact. Salt/pepper appearance		2	1	1		
10		61.71	62.16							
10		62.16	62.48	Grey white clay seam perhaps fault gouge due to abundant slickensides throughout immediate section		3		5		
10		62.48	62.59	Core has been etched and bleached, however, mafics are still intact. Salt/pepper appearance		2	2	1		
10		62.59	63.60							
10		63.60	66.89	At 63.60m is a slickenside surface w/ aspy and ox aspy on contact @ 45° to CA. Another, at 63.92m, slickenside surface @40° to CA.						
10		66.89	68.48	Altered GND, core is bleached to light grey, greenish hue. Minor aspy dissem bits probable that a vein was proximal only lost in recovery. Core becomes gouge/med grey clay. Core is v. broken w/ poor core recovery. Carb in form of veinlets. At 68.63m, a slickenside surface @40° to CA		2	2	1	1	
10		68.48	70.41	Chloritized, altered, bleached GND. Core has slight green hue (chlorite). Core is sericite rich, core can easily be scratched, contains several qtz/carb veins/veinlets @ 68.78: slickenside, 60° @ 69.76: slickenside, 30°		4	2			
10		70.41	72.60							
10		72.60	75.26	Altered GND. Bleached to light grey, green; essentially the selvage around a qtz/carb and sulphide vein/stringers @ 72.68-72.69m, @ 40° to CA. @ 72.60m: slickenside, 35-40° to CA. At 74.73m, slickensides @ 25°-30° to CA.						
10		75.26	75.37	Altered chloritized GND. Selvage around a 0.5cm wide calcite vein		4	2			
10		75.37	76.00							
10		76.00	77.46	Clay gouge w/ qtz eyes, occasional pieces (some w/ slickenside surfaces). Clay is med grey w/ minor sulphide oxidation mixed in	4	3	1	5	1	
10		77.46	81.03	At 77.72m, a slickenside surface, @40° to CA. At 80.60m, slickenside surface @60° to CA, noted that area is altered w/in 2-3cm away		2	2		1	
10		81.03	81.70	Alteration selvage leading to fault gouge @ 81.70 - 81.87m, alteration selvage is light grey-green (chlorite) abundant w/ sericite and devoid of mafics		4	2	0		
10		81.70	82.30	Carbonate stringers w/ aspy and carb veins running ~50° to CA w/in other side of above mentioned alteration selvage from gouge focal point		4	2		5	
10		82.30	82.32	A 2.5cm wide carbonate qtz vein @ 25° to CA w/ ~5% aspy.						
10		82.32	82.56	Alteration selvage continues. @82.56 - slickenside @ 60° to C.A., aspy. on contact surface		4	2		1	
10		82.56	82.74	Clay gouge, light grey clay w/ qtz eyes, aspy disseminated (~5%); contact @ 82.74m is slickensided @ 20° to CA w/ selvage alteration continuing to ~82.94m		4	1	5		
10		82.74	82.83	A qtz/carb vein (1.25cm thick w/ py and aspy) @ 30° to CA is on a site of a fault indicated by slickensides (@ same 30° angle)						
10		82.83	85.69	@85.07: a slickenside, 65°-70° to CA.@85.07: a 1.5cm thick qtz/aspy vein, 65°-70° to CA. Aspy ~20% w/ 10cm wide (either side) chlorite bleached sericite prevalent alteration selvage. Trace py.						
10		85.69	88.94	Core is very broken, yet unaltered. Abundant 'vein like' selvages which are typically @ 40-50° to CA. Broken core is occurring commonly on these vein like selvages, which demonstrate aspy. Core would have an estimate of ~1-3% aspy. Some minor chlorite staining on frac surfaces and occasional slickenside pieces						
10		88.94	89.22	Altered GND. Core is bleached, sericite rich, chloritic stained. Minor mafics visible. Qtz eyes beginning to appear. Aspy stringer/veinlet x-cutting core @ 40-55° to CA, yet sulphides are oxidized mostly	3	3	1	1		
10		89.22	89.95	Core is v. broken, but pieces are demonstrating slickensides on veneers of aspy/calcite. @ 89.92m, slickenside surface of aspy coating. Possible py, 50° to CA.						
10		89.95	90.21	@89.95m: slickenside surface of aspy coating. Possible py, 50° to C.A. Altered selvage GND. Core is light grey-white w/ green (chl) hue. Soft core, abundant sericite w/ trace dissem aspy.		3	1	1		
10		90.21	90.28	White to light grey clay gouge. Qtz eyes		4	1	5		
10		90.28	90.68	Core is v. broken with slickensides on pieces w/ aspy & py & chl on contact surfaces						
10		90.68	91.85	Core is v. broken and is breaking down selvages/veinlets @ 40-60° to CA w/ py and aspy on frac surfaces w/ a lesser extent qtz and carb (sheeted veinlet system may be interpreted)						
10		91.85	92.96							
10		92.96	96.01	GND continues to retain sheeted vein like system. Typical vein/selvage spacing ~ 5cm, and ~55°-60° to CA.						
				From 94.25 to 94.53m, GND becomes slightly bleached and mafics reduce to half regular percentage, w/ a 1cm thick qtz vein, 40° to CA.		1	1			
10		96.01	96.54							
10		96.54	96.80	Core is altered to v. soft. 50% clay, 50% core, core is bleached, yet 5% mafics remain. Chlorite presence gives green hue to colour @ 96.70m: slickensides @ 40-45° to CA.		4	1	3		
10		96.80	97.54	Py and aspy thin frac coating on frac which is along core axis						
10		97.54	98.62							

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, qb = carbonate, b = biotite, qe = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

VEINS											% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
																						B292554	57.91	58.91	0.067		clay zone	VA05047189	1.00	0.211
																						B292555	58.91	59.44	0.067		clay zone	VA05047189	0.53	0.273
																						B292556	BLANK		<0.005			VA05047189		
2	1	0.75	1.25	40	50								5.0									B292557	59.44	60.96	0.037			VA05047189	1.52	
1	1	1.0	1.0	50									1.0									B292558	60.96	62.16	0.012			VA05047189	1.20	0.286
													3.0									B292559	62.16	62.48	0.008		gouge	VA05047189	0.32	
3	1	0.75	1.25	50	35								3.0									B292560	62.48	64.01	0.028			VA05047825	1.53	0.16
3	1	1.0	1.75	50	40																	B292561	64.01	65.53	0.061		qtz + qtz/carb veins	VA05047825	1.52	0.157
3	1	1.0	1.75	50	40																	B292562	64.01	65.53	0.039	DUP	qtz + qtz/carb veins	VA05047825	1.52	
4	1	0.5	2.0	50	60								0.1									B292563	65.53	67.02	0.037			VA05047825	1.49	0.137
																						B292564	67.02	68.58	0.036		broken core/ gouge	VA05047825	1.56	0.165
1	1	0.25	0.25		35					2.0			0.1									B292565	68.58	70.10	0.032			VA05047825	1.52	0.147
1	4	0.25	0.25	35						2.0			0.1																	
2	1	0.5	1.0	40						25.0					1.0							B292566	70.10	70.41	0.076		qtz + carb + sulph veins	VA05047825	0.31	0.174
3	1	0.25	0.75	50	60					0.1												B292567	70.41	71.63	0.043			VA05047825	1.22	
6	1	0.50	3.25	50									5.0									B292568	71.63	73.15	0.049		qtz + qtz/carb veins	VA05047825	1.52	0.231
6	1	0.50	3.25	50									5.0									B292569	71.63	73.15	0.059	PD/CA	qtz + qtz/carb veins	VA05047825	1.52	
																						B292570	STANDARD 3C		0.087	3C		VA05047825		
8	1	0.5	2.25	50									2.0									B292571	73.15	74.68	0.031			VA05047825	1.53	-0.194
1	4	0.75	0.75	50									2.0									B292572	74.68	75.26	0.028			VA05047825	0.58	0.196
2	4	0.5	0.75	50																		B292573	75.26	76.20	0.032			VA05047825	0.94	
																						B292574	76.20	77.46	0.034		broken core	VA05047825	1.26	0.163
9	1	0.5	2.75	40	50					0.1			0.1									B292575	77.46	79.18	0.037			VA05047825	1.72	0.211
																						B292576	BLANK		<0.005			VA05047825		
5	1	0.5	1.75	50		2.0	3			0.1			0.1									B292577	79.18	80.40	0.049			VA05047825	1.22	0.139
4	1	0.5	2.0	40		1.0	2			0.1			0.1									B292578	80.40	81.03	0.054			VA05047825	0.63	0.124
1	4	0.25	0.25	40						0.1			0.1																	
2	1	0.25	0.5	50									8.0									B292579	81.03	82.30	0.072			VA05047825	1.27	
2	4	2.0	2.25	50									5.0																	
1	3	1.5	1.5	30						0.1			1.0									B292580	82.30	82.94	0.068			VA05047825	0.64	
1	6	0.25	0.25	40		1.0	2			0.1			1.0									B292581	82.94	83.82	0.079			VA05047825	0.88	
1	6	0.25	0.25	40		1.0	2			0.1			1.0									B292582	82.94	83.82	0.112	DUP		VA05047825	0.88	
2	1	1.0	2.0	55	70					1.0			5.0									B292583	83.82	85.34	0.079			VA05047825	1.52	
4	1	0.5	2.0	40		0.5	2						0.1									B292584	85.34	86.87	0.073		4 qtz veins and pieces	VA05047825	1.53	
2	1	0.25	0.5	45		1.0	2						3.0									B292585	86.87	88.39	0.082		2 veins and qtz pieces	VA05047825	1.52	
3	1	0.5	2.0	45	50	1.0	2						3.0									B292586	88.39	89.92	0.086		3 veins and pieces	VA05047825	1.53	
4	1	0.5	1.75	40	45	1.0	2						1.0									B292587	89.92	90.68	0.065			VA05047825	0.76	
										1.0			2.0									B292588	90.68	91.44	0.076		v. broken core	VA05047825	0.76	
										1.0			2.0									B292589	90.68	91.44	0.075	PD/CA		VA05047825	0.76	
																						B292590	STANDARD 5E		1.46	5E		VA05047825		
										1.0			1.0									B292591	91.44	92.96	0.075		v. broken core	VA05047825	1.52	
5	1	0.25	1.25	50		1.0	2			10.0			5.0									B292592	92.96	94.49	0.119		py: tr. to 10%	VA05047825	1.53	
4	1	0.25	1.0	45		1.0	2						2.0									B292593	94.49	96.01	0.092			VA05047825	1.52	0.408
										0.1			1.0									B292594	96.01	96.90	0.145		broken core	VA05047825	0.89	0.235
10	1	1.0	6.25	50		1.0	2			2.0			90.0									B292595	96.90	99.06	0.061		aspy: tr. to 90%	VA05047825	2.16	0.218

DRILL LOG LEGEND P1 | DATE: June 6 - 10, 2005 | PAGE 5 of 10

DRILL HOLE # : DG05-280C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; QVE = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		98.62	102.11	Core is abundant w/ fracs (45°-50° to C.A.), common w/ slickensides of aspy/py thus adding to the amount of sheeted veins accounted for.						
10		102.11	117.06	Sheeted veins continue through entire unit, save for bleached altered zone (103.63 - 104.19). Angles typically 40-55° to CA w/ widths ranging from <0.25cm to 0.50cm. Dissem aspy as the predominant sulphide w/ tr po, tr-2% py. Slickensides are common on frac surfaces w/ sulphides on those contacts. Occasional chlorite staining on fracture surface						
				From 103.63 to 104.19m, GND is bleached ,altered zone w/ clay gouge @ ~ 103.74 - 103.89. gouge/pieces of core shows aspy on qtz surfaces, clay is light grey-white	1	2	1	3		
				At 113.53, a 2cm carbonate vein w/ trace aspy (30° to CA) is cross-cut by an aspy veinlet, @45° to CA.						
				From 115.82 to 115.92m, core is altered and bleached, with oxidized aspy, core is easily scratched, sericite is minor to moderate, oxidized aspy veinlets (~5-8%)	2	2	1	1		
10		117.06	117.20	Continued alteration unit as above, core is bleached, however mafics remain, sericite is moderate and grey-looking ox'd aspy is ~5%. Core is easily scratched by a nail, minor clay, some carb veinlets present. Sheeted veining continues at 5-10cm spacing w/ veins/selvages typically 35-50° to CA and <0.75cm wide. Slickensided frac surfaces remain common w/ aspy on surfaces	2	2	1	1	2	
10		117.20	121.42							
10		121.42	121.63	Alteration zone, core is bleached to little or no mafics, sericite and chlorite are prevalent.						
10		121.63	123.44							
10		123.44	129.00	GND begins to bleach out and carbonates begin to pervade the core by coating and veinlets. Core progressively bleaches to ~123.70m where it remains constant until ~129.00m. Core can easily be scratched, qtz veins tough to see because digested; core displays mafics only. Salt and pepper appearance due to bleaching/sericite clay w/ minor chlorite hue. Aspy is present as med-dark grey oxidized veinlets. Core appears as "acid etched"		2	1		2	
10		129.00	130.19							
10		130.19	130.55	Gouge/clay seam, digested bleached core, although some mafic-retained zones. Sericite/chlorite present. Core is v. soft. Contact @130.19m, @20° to CA, cutting veins that are @~ 50°-60° to CA, carbonates present as stringers/veinlets	3	1	1	2		
10		130.55	131.30							
10		131.30	132.02	V. broken bleached/alt'd core. Core reduced to sandy sericite clay w/ some gravel sized pieces. **Note:** still remains a sheeted vn system, vning intensity ebbs & flows. From ~132.0-137.0m: core has a high amount of sheeted vns/meter (~1 per 5cm).		3	2	2	2	
10		132.02	137.09							
10		137.09	137.15	A chlorite/sericite/altered/stained core w/ almost rectangular carbs pass through the core @ ~40-45° to CA. Core immediately surrounding is mafic devoid. No visible sulphides associated.		2	2		2	
10		137.15	138.75	Core is bleached & alt'd to a mafic free, chlorite/sericite prevalent core. Core has greenish hue. Dissem py & aspy around relict selvages/vns/vnlets.		3	2			
10		138.75	139.05							
10		139.05	140.12	Core becomes alt'd grey w/ no visible mafics, sericite & chlorite prevalent. Calcite stringer initially present although they somewhat follow ~50° to CA w/ larger veins.		2	2		2	
10		140.12	140.33	Semi-massive to massive py (85%), aspy (15%) vein. Contact angle @140.33m is @~70° to CA.						
10		140.33	140.60	Grey clay gouge is rich w/ dissem sulphides, although they have been mostly oxidized & thus difficult to discern concentration or percentages of py & aspy. Looks like aspy is prevalent based on grey color & sparkles. Contact @ 140.60m is @30° to CA.						
10		140.60	144.27	Continues to be alt'd & sheeted vn system remains continuous onwards. GND alteration is notably increasing in chlorite, and core is displaying more prominent green color w/ biotite fading.						
10		144.27	144.54	Alt'd GND core is bleached w/ little to no mafics. Core has green hue speckled w/ carb spots (2-5%). Sericite & chlorite present; Core is easily scratched, and is essentially the selvage of py & aspy & sphalerite. Qtz vein @144.53m @40° to CA. Sheet vn system continues.		2	2	1	2	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ca = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5	(0-5)	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
																						B292596	BLANK		<0.005			VA05047825		
9	1	0.75	3.75	45	50	1.0	2			0.1			90.0									B292597	99.06	100.58	0.062		aspy: tr. to 90%	VA05047825	1.52	0.222
2	4	0.1	0.2	45	50																									
4	1	0.5	2.5	50	55	1.0																B292598	100.58	101.05	0.066			VA05047825	0.47	0.29
2	1	2.0	3.0	45	50	1.0	2			2.0			50.0									B292599	101.05	101.66	0.116		aspy: 2-50%	VA05047825	0.61	
4	1	0.5	2.25	45	55	0.5	1			1.0			50.0									B292600	101.66	103.63	0.08		aspy: 2-50%	VA05047825	1.97	0.299
													50.0									B292601	103.63	104.19	0.058		aspy: 2-50% gouge (clay) w/ qtz pieces	VA05047825	0.56	0.49
													50.0									B292602	103.63	104.19	0.086	DUP	aspy: 2-50% gouge (clay) w/ qtz pieces	VA05047825	0.56	
				45	50	0.5	2			2.0			50.0									B292603	104.19	105.16	0.108		aspy: 2-50%	VA05047825	0.97	
													20.0									B292604	105.16	106.68	0.104		v. broken; aspy: tr. to 20%	VA05047825	1.52	0.455
9	1	0.5	6.25	50	55	1.0	1				2.0		50.0									B292605	106.68	108.20	0.116		aspy: 2-50%	VA05047825	1.52	0.499
6	1	0.5	2.75	50		0.5	1						10.0									B292606	108.20	109.73	0.147		aspy: 1-10%	VA05047825	1.53	0.479
10	1	0.75	5.5	50	55	0.25							3.0									B292607	109.73	111.25	0.077		aspy: tr. - 3%	VA05047825	1.52	0.686
9	1	0.75	4.75	50		0.25	1			0.1			30.0									B292608	111.25	112.78	0.07		aspy: tr. - 30%	VA05047825	1.53	0.681
9	1	0.75	4.75	50		0.25	1			0.1			30.0									B292609	111.25	112.78	0.087	PD/CA		VA05047825	1.53	
																						B292610	STANDARD 5E		1.47	5E		VA05047825		
6	1	0.75	3.0	50	55								50.0									B292611	112.78	113.41	0.099		aspy: tr. - 50%	VA05047825	0.63	0.712
1	4	1.5	1.5	30									0.1									B292612	113.41	113.69	0.141			VA05047825	0.28	
1	6	0.25	0.25	45									80.0																	
						0.2	1						5.0									B292613	113.69	114.30	0.058		aspy: tr. - 5%	VA05047825	0.61	
2	1	0.5	1.0			0.2	1			0.1			3.0									B292614	114.30	115.82	0.037		aspy: tr - 3%; 2 veins plus broken pieces	VA05047825	1.52	0.578
9	1	0.5	3.25	35	50	0.1	1						50.0									B292615	115.82	117.35	0.043		aspy: tr. - 50%	VA05047825	1.53	0.393
																						B292616	BLANK		<0.005			VA05047825		
8	1	0.5	3.5	35	50	0.2	1						80.0									B292617	117.35	118.87	0.062		aspy: tr. - 80%	VA05047825	1.52	0.477
				50		0.5	1						3.0									B292618	118.87	120.40	0.093			VA05047825	1.53	0.59
4	1	0.25	2.0	40	60	0.5	1						10.0									B292619	120.40	121.92	0.126		aspy: tr. - 10%	VA05047825	1.52	0.295
10	1	0.5	5.25	45	50	0.5	1						30.0									B292620	121.92	123.44	0.121		aspy: tr. - 30%	VA05047825	1.52	0.358
2	1	0.5	1.0	40	55								3.0									B292621	123.44	124.97	0.047		aspy: tr - 3%	VA05047825	1.53	0.338
2	1	0.5	1.0	40	55								3.0									B292622	123.44	124.97	0.044	DUP		VA05047825	1.53	0.406
													0.1									B292623	124.97	126.49	0.051		bleached/ broken core	VA05047825	1.52	
1	1	1.0	1.0	55									0.1									B292624	126.49	128.02	0.117			VA05047825	1.53	
																						B292625	128.02	129.54	0.137		bleached out	VA05047825	1.52	0.434
6	1	0.5	4.75	50	60								1.0									B292626	129.54	131.06	0.158			VA05047825	1.52	0.335
2	1	0.5	1.0	60	65	0.1	1						5.0									B292627	131.06	132.59	0.229			VA05047825	1.53	0.336
17	1	1.5	9.0	55	60	0.1	1						3.0									B292628	132.59	134.11	0.214			VA05047825	1.52	0.271
17	1	1.5	9.0	55	60	0.1	1						3.0									B292629	132.59	134.11	0.228	PD/CA		VA05047825	1.52	
																						B292630	STANDARD 2B		3.26	2B		VA05047825		
11	1	1.0	6.25	40	60								90.0									B292631	134.11	135.64	0.221		aspy: 0-90% depending on vein	VA05047825	1.53	0.384
1	1	0.25	0.25	20							0.1											B292632	135.64	137.16	0.162			VA05047825	1.52	0.238
18	1	1.5	10.75	50						1.0			1.0																	
4	1	1.0		50	55								1.0									B292633	137.16	137.63	0.386			VA05047825	0.47	0.339
1	1	0.5	0.5	50									50.0									B292634	137.63	138.68	0.167			VA05047825	1.05	
4	6	0.5	2.0	60						40.0																				
2	1			50																		B292635	138.68	139.05	0.058			VA05047825	0.37	0.256
																						B292636	BLANK		<0.005			VA05047825		
																						B292637	139.05	139.80	0.106			VA05047825	0.75	
2	1	1.0	1.5	50						2.0						0.1						B292638	139.80	140.33	1.03			VA05047825	0.53	
1	4	1.75	1.75	55									0.1																	
3	6	10.0	14.0	50	55					85.0			15.0									B292639	140.33	140.60	0.287			VA05047825	0.27	0.484
5	1	0.5	3.0	50	60								1.0									B292640	140.60	141.73	0.066			VA05047825	1.13	
10	1	1.5	7.0	50	60	0.5	2			15.0			10.0									B292641	141.73	143.26	0.232			VA05047825	1.53	0.257
10	1	1.5	7.0	50	60	0.5	2			15.0			10.0									B292642	141.73	143.26	0.377	DUP		VA05047825	1.53	
8	1	0.5	5.25	50	55	2.0	2			0.1			1.0									B292643	143.26	144.27	0.096			VA05047825	1.01	0.294
3	1	0.25	0.75	55	40					0.1			0.1									B292644	144.27	144.78	0.265			VA05047825	0.51	NSS

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005	PAGE 7 of 10		
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMQN = 20; DIOR = 25; MQD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		144.54	158.50							
10		158.50	162.04	Bleached/alt'd zone. Core is light green to light grey-white. Carbs are spotted w/in core like 'olive loaf'. Carb vns & stringer are present. sheeted vning continues, vns are ranging from 0.25-1.5cm thick and angle to CA has increased to ~70-75° to CA.		4	3	1	2	
10		162.04	163.65							
10		163.65	164.12	Sulphide qtz vn contacts @~65-70° to CA. 20-25% py & 20-25% aspy, sulphides are dissem throughout, but are somewhat oriented ~70° to CA (see photo). Surrounding core is alt'd to sericite/chlorite, yet coherent core.		2	2	1	1	
10		164.12	164.55							
10		164.55	165.03	Qtz sulphide vn w/ 2% aspy & ~2% py. Sulphide vnlets in vn are @~60-70° to CA.						
10		165.03	168.42	At 167.52m a slickenside @20° to CA, aspy on surface sheared & partially oxidized.						
10		168.42	168.64	Qtz/carb semi-massive py/aspy vn @~65-70° to CA. Alt'd selvage is continuous to 169.55m. Alt'n is abundant w/ sericite, minor chlorite (5%), little to no mafics, core is bleach & scratchable w/ a nail. Sheeted vning continues w/ spacing of vns/vnlets @~2-5cm apart w/in selvage.	1	3	2		2	
10		168.64	170.06							
10		170.06	170.69	Highly alt'd selvage leading to fault gouge clay @170.69-170.76m. Selvage is sericite abundant (25-30%), chlorite is ~5-8%. No mafics visible, minor relict qtz vns highlighted by aspy dissems or stringer @ typical 60-70° to CA.		4	2		2	
10		170.76	172.21	Core is mod alt'd, little to no mafics, essentially all selvage.		4	2	1	2	
10		172.21	172.49							
10		172.49	174.71	Core is mod alt, little to no mafics, essentially all selvage.		4	2	1	2	
10		174.71	175.26							
10		175.26	175.43	Core is extremely bleached & etched yet v. coherent (looks sand blasted & acidified). Stringers of py & aspy run w/ some minor direction ~70-80° to CA. Sericite & chlorite present.		3	2	2	1	
10		175.43	177.60							
10		177.60	177.64	A 4cm wide qtz/aspy (15%) vn @80° to CA. Alt'd selvage large & alt'n is significant.	1	4	2			
10		177.64	178.56							
10		178.56	181.36	Sheeted vning continues @70-80° to CA w/ spacing ~@5-8cm at most. From 181.36-182.66m, core is too alt'd to see vning system, yet continues from next box over.						
10		181.36	184.24							
10		184.24	185.93	Alt'd selvage that appears to be focused from a qtz/carb vn that's 6cm wide @45° to CA w/ 5-8% py & 3-5% aspy. @~185.29-185.93m. Alt'n intensifies to a category 4-5. Core is v. bleached, mafic free, w/ only sulphide stringers of ox'd py & aspy w/ abundant sericite & less chlorite. Dissems w/ GND perhaps not related to vning may be occurring but not observable enough to conclude for certain.		4	2	1	3	
10		185.93	190.50							
10		190.50	197.62	Sulphides, predominantly aspy, is being deposited via vnlets & stringers <0.1cm or mm sizes of qtz & carbs x-cutting larger vns, etc. Core would be estimated to contain ~2-3% sulphides total as a result. Sheeted vns appear to have disappeared but perhaps they haven't but the alt'n relicted the vns & discerning vns is no longer possible.		2	2		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

		VEINS								% of VEIN & DISSEMINATED MATERIAL																									
							Selvages			Sulphides										Oxidation															
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
1	6	1.5	1.5	40					55.0			35.0		2.0																			
									0.1			5.0									B292645	144.78	146.30	0.14		x-cutting carb stringers	VA05047825	1.52	
5	1	1.0	5.5	40	70				0.1			30.0									B292646	146.30	147.83	0.152		aspy: tr to 30%, depending on vein	VA05047825	1.53	0.287
15	1	1.0	6.0	70	60	27	2		2.0			20.0									B292647	147.83	149.35	0.103		aspy: tr. To 20%, depending on vein	VA05047825	1.52	0.343
6	1	0.5	5.5	60	70	61.0	3					40.0									B292648	149.35	150.88	0.108		aspy: trace to 40%, depending on vein	VA05047825	1.53	0.308
6	1	0.5	5.5	60	70	61.0	3					40.0									B292649	149.35	150.88	0.104	PD/CA		VA05047825	1.53	
																					B292650	STANDARD 6F		2.48	6F		VA05047825		
15	1	0.5	9.0	65	70	2.0	2					5.0									B292651	150.88	152.40	0.122			VA05047825	1.52	0.319
16	1	0.5	6.5	65	70	0.2															B292652	152.40	153.92	0.041			VA05047825	1.52	
11	1	2.0	7.0	65	70	17.0	4	2	1.5			20.0									B292653	153.92	155.45	0.062		aspy: tr. To 20%, depending on vein	VA05047825	1.53	
7	1	0.75	2.75	50	70	27	3	2				5.0									B292654	155.45	156.97	0.123			VA05047825	1.52	
8	1	0.5	5.5	70								10.0									B292655	156.97	158.50	0.094		aspy: tr. To 10%, depending on vein	VA05047825	1.53	
																					B292656	BLANK		<0.005			VA05047825		
5	1	0.5	3.75	70	60	150	4	1				10.0									B292657	158.50	160.02	0.162		aspy: tr. To 10%, depending on vein	VA05047825	1.52	
8	1	2.75	7.5	60	70	150	3	1													B292658	160.02	161.54	0.318			VA05047825	1.52	
2	4	2.0	3.0	70					0.1			1.0																					
1	6	0.5	0.5	65					70.0			20.0																					
14	1	1.5	10.25	70	80	20	3					2.0									B292659	161.54	163.07	0.131			VA05047825	1.53	
7	1	3.0	6.0	70		33	3	1	2.0			10.0									B292660	163.07	163.70	1.17		aspy: tr. To 10%, depending on vein	VA05047825	0.63	
1	6	35.75	35.75	65	70	43	4		25.0			25.0									B292661	163.70	164.12	0.529			VA05047825	0.42	
1	6	35.75	35.75	65	70	43	4		25.0			25.0									B292662	163.70	164.12	0.615	DUP		VA05047825	0.42	
2	1	1.5	2.0	70								30.0									B292663	164.12	164.59	0.865		aspy: tr. To 30%, depending on vein	VA05047825	0.47	
1	1	42.0	42.0	70		78	4	2	2.0			3.0									B292664	164.59	165.03	0.78			VA05047825	0.44	
5	1	0.5	3.5	75	80				25.0			25.0									B292665	165.03	166.12	0.167			VA05047825	1.09	
9	1	5.0	11.5	70	75	23	3	1	2.0			10.0									B292666	166.12	167.64	0.468			VA05047825	1.52	
6	1	1.25	5.0	70					1.0			2.0									B292667	167.64	168.42	0.341			VA05047825	0.78	
1	3	12.0	12.0	60	70	150	4	1	25.0			10.0		8.0		8.0					B292668	168.42	168.64	1.35		other' is carb	VA05047825	0.22	
1	6	3.25	3.25	65	70	150	4	1	100.0																								
1	3	12.0	12.0	60	70	150	4	1	25.0			10.0		8.0		8.0					B292669	168.42	168.64	1.38	PD/CA		VA05047825	0.22	
1	6	3.25	3.25	65	70	150	4	1	100.0																								
																					B292670	STANDARD 7G		4.57	7G		VA05047825		
2	1	0.5	1.0	65								1.0									B292671	168.64	169.16	0.207			VA05047825	0.52	
17	1	1.0	7.25	75	80	150	3		0.1			15.0									B292672	169.16	170.69	0.186		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
17	1	1.0	10.5	70	75	150	3					15.0									B292673	170.69	172.21	0.22		aspy: tr. To 15%, depending on vein	VA05047825	1.52	
13	1	1.5	8.0	70	75	120	3		0.1			15.0									B292674	172.21	173.74	0.219		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
10	1	1.0	6.25	60	70	150	3		0.1			1.0									B292675	173.74	175.26	0.212			VA05047825	1.52	
																					B292676	BLANK		<0.005			VA05047825		
7	1	1.25	4.75	75	80	150	3	2	20.0			25.0									B292677	175.26	176.25	0.167		py: tr. To 20%, depending on vein aspy: tr to 30%, depending on vein	VA05047825	0.99	
13	1	0.5	6.0	70		0.1	1					0.1									B292678	176.25	176.78	0.114			VA05047825	0.53	
26	1	4.25	17.0	75	80	32	2		0.1			15.0									B292679	176.78	178.31	0.24		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
14	1	0.5	8.75	65	80							3.0									B292680	178.31	179.67	0.099		aspy: tr. To 3%	VA05047825	1.36	
14	1	0.25	6.25	65	70				1.0			5.0									B292681	179.67	180.22	0.124		aspy: tr. To 5%, depending on vein	VA05047825	0.55	
1	4	1.5	1.5	65	70																												
14	1	0.25	6.25	65	70				1.0			5.0									B292682	179.67	180.22	0.173	DUP		VA05047825	0.55	
1	4	1.5	1.5	65	70																												
7	1	0.5	5.25	70	80							2.0									B292683	180.22	181.26	0.145			VA05047825	1.04	
5	1	0.5	2.75	65	70	74	5					5.0									B292684	181.26	182.12	0.103		aspy: tr. To 5%, depending on vein	VA05047825	0.86	
2	1	0.25	0.5	70								0.1									B292685	182.12	182.58	0.071			VA05047825	0.46	
1	4	0.75	0.75	70		42	5					2.0																					
25	1	1.0	8.0	60	70							0.1									B292686	182.58	184.24	0.081			VA05047825	1.66	
3	4	6.0	8.0	45	75	162	4		8.0			5.0		1.0							B292687	184.24	185.93	0.761		aspy: tr. To 5%, depending on vein	VA05047825	1.69	
				60	65				1.0			5.0									B292688	185.93	187.45	0.14		aspy: tr. To 5%, depending on vein too altered to see	VA05047825	1.52	
				60	65				1.0			5.0									B292689	185.93	187.45	0.127	PD/CA		VA05047825	1.52	
																					B292690	STANDARD 4D		0.461	4D		VA05047825		
10	1	0.5	5.25	75	80							0.1									B292691	187.45	188.98	0.023			VA05047825	1.53	
1	4	1.0	1.0	50								0.1																					
																					B292692	188.98	189.86	0.04		too alt'd to see	VA05047825	0.88	
2	1	1.5	2.0	70	75							0.1									B292693	189.86	190.60	0.03			VA05047825	0.74	

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005	PAGE 9 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAM = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				At 195.58, the core becomes extremely alt'd to sericite & chlorite. The core is mafic-devoid & sulphides are ox'd almost completely. Some carb vnlets are preserved. Qtz eyes are small yet give core texture. Core almost is pure white in places yet core is competent, not clay. Appears as core has undergone acid etching from hot hydrofluids. At 195.95m a slickenside @ 40° to CA w/ a black graphitic looking ox'n product forming a thick coating (1-2mm) w/ slickensides on it		4	2		1	
10		197.62	198.35	The core is riddled w/ sulphide vnlets of py/aspy & ox'd sulphides. There is an abundance concentrated from 197.86-198.20m @~50% sulphides, ox'n is either high causing thick black graphite-like build up or it bismuthinite (unsure). Sulphides has relative angle of orientation @~40-55° to CA (see photos).						
10		198.35	202.78	Core becomes v. salt and pepper bleached w/ stringers & vnlets of predominantly aspy or ox'd grey sulphides throughout. Typical angle on discernable vns/vnlets @60-70°. To end of hole continued w/ unalt'd GND w/ fracs typical @60-85° to CA w/ some fracs occurring on vnlets of sulphides.		1	0	0	2	
10		202.78	206.65							
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvage Alteration: phl = chlorite, k = K-spar, s = sericite, q = quartz/silica, ob = carbonate, b = biotite, oe = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 6 = quartz/chlorite, 8 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages			Sulphides									Oxidation				Sample Number				sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration (0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To	Au (g/T)					
1	4	4.0	4.0	55	60	71.0	3		0.1																					
8	1	1.0	5.75	70		38	4	2				15.0									B292694	190.60	192.02	0.079			VA05047825	1.42	
13	1	0.75	5.75	45	60	150	2	1													B292695	192.02	193.55	0.073			VA05047825	1.53	0.351
																					B292696	BLANK		<0.005			VA05047825		
												10.0									B292697	193.55	195.07	0.038		none visible due to alt'n	VA05047825	1.52	0.228
																					B292698	195.07	196.50	0.143			VA05047825	1.43	0.35
																					B292699	196.50	197.62	0.078			VA05047825	1.12	0.286
																					B292700	197.62	198.35	1.165			VA05047825	0.73	
																					B292701	198.35	199.64	0.065			VA05047825	1.29	0.295
																					B292702	198.35	199.64	0.047	DUP		VA05047825	1.29	
1	4	0.5	0.5	50								0.1									B292703	199.64	201.17	0.055			VA05047825	1.53	0.264
1	6	0.5	0.5	80								20.0					5.0				B292704	201.17	202.69	0.061			VA05047825	1.52	0.273
3	1	1.0	2.5	65					0.1			3.0									B292705	202.69	204.22	0.118		aspy: tr. To 5%, depending on vein	VA05047825	1.53	0.325
7	1	0.5	4.0			6.0						20.0					4.0				B292706	204.22	205.74	0.049		aspy: tr. To 20%, depending on vein	VA05047825	1.52	0.343
																					B292707	205.74	206.65	0.022			VA05047825	0.91	
																					EOH								

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-281C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1001m

BEARING: 000 | DIP: -50°

DATE STARTED: June 8, 2005 (night) | DATE COMPLETED: June 11 (day)

COORD SYSTEM: NAD 27: EASTING: 459631 NORTHING: 7099239

COORD SYSTEM: NAD 83: EASTING: 459512 NORTHING: 7099424

NAD 27 (CORRECTED for historic grid): EASTING: 459601 NORTHING: 7099249

LOGGED BY: M. Stone

SECTION LINE(historic grid): 459601E

CONTRACTOR: Britton Brothers

SAMPLING DETAILS

Sample Sequence: B291824 - B292033

Requisition #: MASP448STRGOL.05Q | Date Shipped: 14-June-05

Lab Record #: VA05049846 | Date Received: 24-June-05

DRILLING DETAILS

Hole Diameter: HQ

Overburden: to 24.38m

Deviation:

Casing: 24.38m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

Duplicates:	B291842, B291861, BB291883, B291902, B291922, B291942, B291962, B291981, B292002, B292022
Preparation Duplicate/ Check Assay:	B291829, B291850, B291869, B291889, B291909, B291929, B291949, B291969, B291989, B292009, B292029
Standards:	B291830, B291850, B291870, B291890, B291910, B291930, B291950, B291970, B291990, B292010, B292030
Blanks:	B291836, B291856, B291876, B291716, B291936, B291956, B291970, B291990, B292016,

FROM	TO	LITHOLOGY
24.38	43.65	MSED
43.65	222.5	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	335.9	48	001.9	002.9
150	338.1	48.2	004.1	005.1
222.5	337	47.4	003	004

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: 8 to 11-June-05 PAGE	of 14		
DRILL HOLE #: DG05-281C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-24.38	0.00	24.38	Casing						
80	24.38-43.65	24.38	25.91	10cm GND section (24.38-24.48m); followed by metaseds w/ v. finely-laminated (<1mm) bedding, well-preserved w/ subtle compositional variation (i.e. more mafic/more felsic) btwn layers. Pure qtz pebbles make up 20% of total pebbles, have metaseds on margins so veining exists w/in metaseds. Ox'n through whole core.	3			1		
80		25.91	27.73	Metaseds as described above. One qtz vein offset by microfracture. Microfrac has same strike as bedding but cuts across w/in core. Strike 40° to CA.	2		1	1		
80		27.73	32.22	Gouge. Gravel to clay texture. V. few relicts of metaseds, pieces up to 6cm (qtz eyes or coherent mafic beds). Purple hue to some sections - high hematite content. Other zones have euhedral hematite grains ~2mm diameter. Color light yellowish brown w/ lenses ~1cm wide of pale whitish blue, dark brown, mustard yellow.	4	1		4		
80		32.22	33.74	Back to competent, moderately oxidized argillite as described above. Bedding @ 30° to CA. Beds have been moved along micro-fractures.	3	1		1		
80		33.74	36.45	Gouge as above (27.73-32.22m). Remnant hematitic bedding @ 34.4m, @ 25° to CA. Hematite crystals w/in qtz vns (2%).	4	1		4		
80		36.45	37.50	Gouge w/ qtz section 15cm wide.	3	1		3		
80		37.50	39.62	Clay to sandy-textured alt'd metaseds, 20% pebbles 1cm-4cm.	4	1		4		
80		39.62	43.65	GND infiltrates metaseds in 40cm, 30cm & 10cm sections. Carb (calcite) on frac faces.	3	1		1	1	
10	43.65-222.50	43.65	44.20	Unalt'd GND w/ carb/qtz veins & qtz veins w/ ~1cm selvages.	1				1	
10		44.20	45.62	Unalt'd GND except on fractures & micro-fractures where limonite is, and around qtz vns w/ tiny selvages.	1				1	
10		45.62	47.14	Calc & lim throughout GND veinlets & matrix. Crumbly texture.	2			1	2	
10		47.14	49.29	More competent GND w/ lim & calcite on fractures	1				1	
10		49.29	53.34	Crumbly GND w/ lim on micro-fractures & through matrix.	3	1		2	2	
10		53.34	54.86	8cm competent GND & gouge material in 10cm length.	3			2	2	
10		54.86	57.60	Competent but crumbly core, lim & calcite pervasive.	3			1	2	
10		57.60	61.34	1mm-2mm thick encrustations of lim on frac surfaces; calcite inside that layer, and through cracks in qtz vns.	2		1		1	
10		61.34	62.66	22cm gouge zone surrounded by 50cm selvage of alt'd GND. Color of alt'd material (selvage) is light brown. Gouge is whitish orange w/ pale blue/white clayey material w/ gravel-size qtz eyes/oxidized GND.	3	2	1	3	1	
10		62.66	64.01	Limonite stained, v. broken GND.	2	2	1	1	1	
10		64.01	65.53	Mod'ly alt'd GND. Few unalt'd sections (5cm long); rest pervaded w/ limonite.						
10		65.53	66.14	Minor alt'd GND. Ox'd selvages around qtz vns; calcite 1mm vnlets w/in veins & GND.	1	1	1		1	
10		66.14	67.06	Highly alt'd GND, limonite throughout matrix & veinlets. Color is pale greenish-yellowish brown & texture is clay to gravel. Common veinlet direction 10° to CA.	2	2	1	1	1	
10		67.06	67.47	Gouge to clay to sand texture. Slickensides defined in limonite/calcite fracture @ 25° to CA.	3	2	2	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To							
2	1	4.0	4.5			0.4	q	2	2													B291824	24.38	25.91	0.020		qtz pieces	VA05049846	1.53	1.3	
8	1	3.0	11	35	20	0.5	q	2	2													B291825	25.91	27.43	0.009			VA05049846	1.52	5.3	0.277
2	1	0.5	1.0	15		0.5	q	2	1	2.0								5.0				B291826	27.43	27.73	0.026			VA05049846	0.30	6.7	0.174
2	1	0.3	0.6	15		1.0	q	2	2													B291827	27.73	28.96	0.089			VA05049846	1.23	1.6	
																						B291828	28.96	30.48	0.016			VA05049846	1.52	0.0	0.062
																						B291829	28.96	30.48	0.017	PD/CA		VA05049846	1.52	0.0	
																						B291830	STANDARD 5E		1.265	5E		VA05049846			
																						B291831	30.48	31.10	0.132			VA05049846	0.62	0.0	0.245
																						B291832	31.10	32.22	0.087			VA05049846	1.12	0.0	
3	1	1.8	2.4	50	55	6.0	q	1	2													B291833	32.22	33.74	0.013			VA05049846	1.52	2.0	0.326
																						B291834	33.74	35.06	0.032			VA05049846	1.32	0.0	NSS
2	1	1.0	2.0							2.0								5.0				B291835	35.06	36.58	1.020		qtz pc's, selvage gouged	VA05049846	1.52	1.3	0.13
																						B291836	BLANK		<0.005			VA05049846			
3	1	15	17	80																		B291837	36.58	37.50	0.062			VA05049846	0.92	3.3	0.486
																						B291838	37.50	38.13	0.585			VA05049846	0.63	0.0	
																						B291839	38.13	39.62	0.294			VA05049846	1.49	0.0	0.556
																						B291840	39.62	40.90	0.463			VA05049846	1.28	0.0	0.918
																						B291841	40.90	41.80	1.245			VA05049846	0.90	0.0	0.96
																						B291842	40.90	41.80	0.767	DUP		VA05049846	0.90	0.0	
2	1	1.2	2.4	80		4.0	q	3	1	2.0								5.0				B291843	41.80	43.65	0.383			VA05049846	1.85	1.1	0.769
8	3	0.5	2.0	80		1.0	q	3	3													B291844	43.65	44.20	0.099			VA05049846	0.55	14.5	
							cb	1																							
1	1	1.0	1.0	80		1.0	q	2	1												1.0						other' is hematite				
4	1	1.0	4.0	70		0.5	q				7.0											B291845	44.20	45.62	0.164			VA05049846	1.42	2.8	0.743
1	1	1.0	1.0	70		2.0	q	3													1.0	B291846	45.62	47.14	0.546		other' is hematite	VA05049846	1.52	0.7	1.59
							chl	3																							
																						B291847	47.14	47.87	0.086			VA05049846	0.73	0.0	0.46
																						B291848	47.87	48.43	0.063			VA05049846	0.56	0.0	0.936
																						B291849	47.87	48.43	0.089	PD/CA		VA05049846	0.56	0.0	
																						B291850	STANDARD 6F		2.680	6F		VA05049846			
																						B291851	48.43	49.29	0.724			VA05049846	0.86	0.0	
																						B291852	49.29	50.29	0.180			VA05049846	1.00	0.0	
																						B291853	50.29	51.82	0.332			VA05049846	1.53	0.0	2.27
																						B291854	51.82	53.34	0.150			VA05049846	1.52	0.0	1.32
																						B291855	53.34	54.50	0.598			VA05049846	1.16	0.0	1.045
																						B291856	BLANK		<0.005			VA05049846			
																						B291857	54.50	54.86	0.153			VA05049846	0.36	0.0	
																						B291858	54.86	56.19	0.360			VA05049846	1.33	0.0	1.06
2	1	1.0	1.5	60		2.0	q	3	2													B291859	56.19	57.60	0.911			VA05049846	1.41	1.4	0.934
							chl	1																							
4	1	1.0	2.5	65	60	2.0	q	3	1												1.0	B291860	57.60	59.27	0.179		other' is hematite	VA05049846	1.67	2.4	1.1
							s	1																							
4	1	4.0	12	60		2.0	q						5.0								1.0	B291861	59.27	60.76	4.050		other' is hematite	VA05049846	1.49	2.7	5.65
4	1	4.0	12	60		2.0	q						5.0								1.0	B291862	59.27	60.76	0.814	DUP		VA05049846	1.49	2.7	
2	1	0.6	1.2	60		0.5	q	1	2													B291863	60.76	61.34	0.870			VA05049846	0.58	3.4	1.48
							chl	1																							
																						B291864	61.34	62.66	0.386			VA05049846	1.32	0.0	
1	1	1.0	1.0	60		1.0	q	3	1													B291865	62.66	64.01	0.186			VA05049846	1.35	0.7	0.642
							chl	1																							
							s	2																							
3	1	2.0	5.0	50	60	3.0	q	1		0.1			4.0					5.0	4.0			B291866	64.01	65.53	0.350			VA05049846	1.52	2.0	2.48
							chl	1																							
							s	2																							
3	1	1.0	3.0																			B291867	65.53	66.14	0.438			VA05049846	0.61	4.9	0.805
																						B291868	66.14	67.06	0.156			VA05049846	0.92	0.0	
																						B291869	66.14	67.06	0.226	PD/CA		VA05049846	0.92	0.0	
																						B291870	STANDARD 6F		2.750	6F		VA05049846			
1	1	1.0	1.0	35		0.5	q	3	2													B291871	67.06	67.47	1.040			VA05049846	0.41	2.4	0.628
							chl	1																							

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION — Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		67.47	69.03	Limonite 90% pervasive in section, 10% unalt'd GND. Randomly-oriented calcite veinlets throughout.	3	2	2	1	1	
10		69.03	69.41	GND stained brown w/ little original texture remaining.	3	2	1	1	1	
10		69.41	70.31	Unalt'd GND & vns of qtz w/ moderate selvages. Lim & carb in less frequent veinlets.	1	1	1		1	
10		70.31	70.65	Limonite and carbonate staining pervasive. Overall, colour is light brown. 40% clay weathering makes rock weak but competent except 4cm gouge (clay)	3	3	1	2	1	
10		70.65	72.11	Limonite and carb less prevalent, but seen on ragged veinlets, generally trending ~10° to CA. Unaltered GND where not affected by sheeted vein set: 50% veins broken up (just linear qtz chunks)	1	1			1	
10		72.11	73.60	Limonite and carbonate pervading GND to weaker, but coherent core as at 70.31-72.11m. Early in sample, low angle fracture face shows lineated calcite (drawn - 40° to CA)	3	3	1	1	2	
10		73.60	74.46	Very weak rock due to pervasive limonite and calcite in < 0.2cm widths	3	2	1	2	1	
10		74.46	75.56	Sample is ~35% massive qtz, probably broken up and compacted old veins. GND weakened by pervasive lim and calcite.	3	2			2	
10		75.56	76.65	V. crumbly and clay-rich GND altered through pervasive limonite and calcite	3	4	1	2	2	
10		76.65	78.07	Sand-size material to GND chunks up to ~5cm.	4	3	1	2	1	
10		78.07	79.25	Extremely altered to white/brown clay-rich matrix. Calcite notable throughout.	3	3	1	1	2	
10		79.25	83.82	Gouge to crumbly, sericitized GND. Slickenside in muddy black clay on fract @10° to CA.	4	4	2	3	2	
10		83.82	84.60	Competent unaltered to moderate altered GND	1	2	1		1	
10		84.60	85.96	Old qtz/carb veins(@55°) overprinted by veinlets of limonite and calcite to 10°/110°. Veinlets have 2mm selvages. Very broken core, poor recovery here as well	2	2	1		2	
10		85.96	86.16	Sand. Pure. Medium brown	2					
10		86.16	87.51	Same as 85.60-85.96m, but more frequent carb/qtz veins. Lim covers fracture faces, at regular angles of 50/140°	1	1	1		1	
10		87.51	88.08	Unaltered GND w/ qtz veins and few lim veinlets. Ragged orientations, lim on straight fract too	1	1	1		1	
10		88.08	88.49	Calcitic and silica alteration more prevalent. Low angle fracture (10° to CA) w/ slickensides of ser and chl	1	1	1		2	
10		88.49	89.92	Lim/calc veinlets (1mm) weaken rock to v. broken. Texture of GND appears silicified, crystalline	2	2			1	
10		89.92	91.44	Few preserved sections of unalterd GND. 80% limonite stained, so pervasively that GND texture is erased	3	3	2		1	
10		91.44	92.96	30% unaltered GND w/ >2cm qtz veins w/ wide selvages	2	3	1		1	
10		92.96	93.61	Coherent, unaltered GND to 93.5m, where GND is limonized and brown coloured	1	1	1		1	

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides									Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To							
																						B291872	67.47	69.03	0.427			VA05049846	1.56	0.0	0.262
2	1	2.0	2.5	60		2.0	q	2														B291873	69.03	69.41	0.313			VA05049846	0.38	5.3	
							s	3																							
6	1	2.0	5.0	60		2.0	q	3		8.0								4.0				B291874	69.41	70.31	0.286			VA05049846	0.90	6.7	
							s	3																							
							chl	1																							
0																						B291875	70.31	70.65	2.840			VA05049846	0.34	0.0	1.02
																						B291876	BLANK		<0.005			VA05049846			
8	1	2.0	10.0	45		5.0	q	2	1	0.1			0.1					5.0	5.0			B291877	70.65	72.11	0.696			VA05049846	1.46	5.5	4.05
							s	3																							
1	6	1.0	1.0	60		1.0	chl	2		5.0	15.0		10.0					4.0	4.0												
							q	2																							
4	1	1.2	2.8	60		2.0	q	1	2	3.0			2.0					4.0	4.0			B291878	72.11	73.60	0.956			VA05049846	1.49	2.7	
							s	4																							
2	1	1.0	2.0	90		10.0	q	4	4	3.0			2.0					4.0	4.0			B291879	73.60	74.46	0.829			VA05049846	0.86	2.3	
3	1	1.2	5.0	60						8.0			5.0					4.0				B291880	74.46	75.56	1.095		selvage indistinct	VA05049846	1.10	2.7	3.17
1	4	1.0	1.0			3.0	q	2	1				5.0						3.0												
							cb	2																							
							chl	1																							
0																						B291881	75.56	76.65	0.401			VA05049846	1.09	0.0	
0																						B291882	75.56	76.65	0.271	DUP		VA05049846	1.09	0.0	
1	1	0.8	0.8	75		2.0	q	3	4				0.1						5.0			B291883	76.65	78.07	0.847			VA05049846	1.42	0.7	1.85
							s	3																							
1	4	2.0	2.0	80		5.0	cb	3	4													B291884	78.07	79.25	0.296			VA05049846	1.18	0.8	1.925
							chl	1																							
0																						B291885	79.25	80.77	0.394			VA05049846	1.52	0.0	2.63
																						B291886	80.77	82.30	0.317			VA05049846	1.53	0.0	1.735
																						B291887	82.30	82.80	0.283			VA05049846	0.50	0.0	2.19
																						B291888	82.80	83.82	0.691			VA05049846	1.02	0.0	
																						B291889	82.80	83.82	0.532	PD/CA		VA05049846	1.02	0.0	
																						B291890	STANDARD 1A		0.930	1A		VA05049846			
7	3	0.3	2.1	55		2.0	q	2		2.0								2.0				B291891	83.82	84.60	0.246			VA05049846	0.78	9.0	2.84
							s	3																							
							chl	1																							
																						B291892	84.60	85.96	0.295			VA05049846	1.36	0.0	1.495
																						B291893	85.96	86.16	0.324			VA05049846	0.20	0.0	
11	3	2.0	4.5	80	65	1.0	q	1	1	1.0			1.0					4.0	4.0			B291894	86.16	87.51	0.218			VA05049846	1.35	8.1	1.625
							s	1																							
							chl	1																							
3	3	1.0	3.0	60		2.0	q	2	3		0.1		1.0						4.0			B291895	87.51	88.08	0.392			VA05049846	0.57	5.3	
							s	2																							
							chl	1																							
5	3	1.0	4.0	70	60	8.0	q	2	1				1.0						4.0			B291896	88.08	88.49	0.045		Missed Blank Stamp	VA05049846	0.41	12.2	0.974
							s	2																							
							chl	2																							
																						B291897	88.49	89.92	0.269			VA05049846	1.43	0.0	
3	1	1.0	3.0	55		15.0	q	3	3	20.0								2.0				B291898	89.92	91.44	0.294			VA05049846	1.52	2.0	0.717
							s	3																							
							chl	3																							
5	1	4.0	7.0	45		4.0	q	4		5.0			3.0					5.0				B291899	91.44	92.96	0.100			VA05049846	1.52	3.3	0.686
							s	3																							0.901
							chl	1																							
0																						B291900	92.96	93.61	0.038			VA05049846	0.65	0.0	0.634

DRILL LOG LEGEND P1	DATE: 8 to 11-June-05	PAGE 5 of 14	
DRILL HOLE #: DG05-281C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		93.61	94.49	Heavily broken and limonized GND. Calcite and chlorite on fracture faces w/ no lineation	2	2	1		1	
10		94.49	95.59	Unaltered GND except selvages, around qtz veins and 1-2mm around veinlets/fractures covered w/ limonite and calcite	1	1	1			
10		95.59	96.01	Limonized and broken GND; weak and crumbly grey qtz vein	2	2	1		1	
10		96.01	97.54	Unaltered GND except carb + lim veinlet/fract w/ 1-2mm selvage. Larger qtz veins have weak silica-defined selvage	1	1			1	
10		97.54	99.06	Extremely altered GND. Chlorite, sericite, limonite throughout (colourful - yellow, orange speckles, greenish greyish brown). Original GND texture completely overprinted by alteration. Carbonate throughout as well (yellow part)	3	4	3	2		
10		99.06	100.58	Unaltered GND w/ qtz and qtz/carb veins w/ selvages (increased chlorite)	2	1	2		1	
10		100.58	103.26	Unaltered GND w/ qtz and qtz/carb veins w/ selvages (increased chlorite)	2	1	2		1	
10		103.26	104.12	Limonized and silicified GND gouge (yellowish brown) to competent (yellowish grey). Gouge section from 104.0 - 104.2m.	2	3	3	2	2	
10		104.12	104.64	Mod. Altered GND. Low angle (near parallel to CA.) veinlets (1-2mm) covered in lim and calcite. Also in random orientations	1	1	1		1	
10		104.64	105.80	Alt'd GND. Lim pervasive through 90%, rest is silicified. One small lens of ox'd sulphides @ 105.7m, 1mm wide, 3cm long, black	3	3		4	2	
10		105.80	106.43	Pale bluish white clay altered w/ veinlets, limonized (random) Hematite oxidized in qtz vein colours it pink	1	4	1	4	1	
10		106.43	107.32	V. mafic GND (qtz preferentially dragged to vein?) Separated by lim/q/cb alteration around qtz veins	1	3	1		1	
10		107.32	108.20	Extremely alt'd GND, colourful, as at 97.54- 99.06m. Lim fractures parallel to CA. Ser and chl on fract to 25° to C.A. Lim staining for 10cm (pervasive)	3	3	3	2	2	
10		108.20	109.73	Unaltered GND separated by selvages around qtz and carb veins. One qtz vein offset on 1mm fracture. Sericite lineation on fract face (10° to CA).	2	2		1	2	
10		109.73	110.35	Mod'ly alt'd GND; selvages oxidized	2	2	1		2	
10		110.35	111.05	Extremely altered GND, pale bluish white. Carb appears pervasive, stemming from randomly oriented veinlets throughout	1	4	2	3	4	
10		111.05	112.13	Extremely altered GND stained black, soft, flakey mineral	1	4	2	3	2	
10		112.13	125.51	Chloritized, clay-altered GND w/ <20cm blackened sections. Only slight variation in composition throughout. Overall colour is pale bluish green, and either white or black. Soft, clay to crumbly texture. @120.40m, a lens of grey clay w/ lineation, drawn, face is at 50° to CA.	1	4	3	3	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To							
4	1	0.5	2.0	15		5.0	q	3	1				5.0						2.0			B291901	93.61	94.49	0.201			VA05049846	0.88	4.5	
							chl	2																							
							s	2																							
																						B291902	93.61	94.49	0.092			VA05049846	0.88	0.0	
3	1	1.5	3.5	35		5.0	q	1		0.1								5.0				B291903	94.49	95.59	0.144			VA05049846	1.10	2.7	0.941
							chl	1																							
							s	1																							
2	3	0.5	1.0	45		1.0	q	3										1.0				B291904	95.59	96.01	0.417			VA05049846	0.42	4.8	
							cb	3																							
1	1	1.0	1.0	70																											
6	1	3.0	9.0	55		1.0	q	1	1	2.0			0.1					5.0				B291905	96.01	97.54	0.172			VA05049846	1.53	3.9	0.533
6	1	1.0	5.0	70			q	4	3				5.0									B291906	97.54	99.06	0.295			VA05049846	1.52	3.9	1.35
							s	4																							
							ch	3																							
5	3	2.0	5.0	30		10.0	q	4					5.0						2.0			B291907	99.06	100.58	0.447			VA05049846	1.52	3.3	0.704
							cb	4																							
							chl	3																							
6	3	2.0	4.0	60	45	2.0	q	3	1	4.0			12.0					4.0				B291908	100.58	102.11	0.158			VA05049846	1.53	3.9	0.557
							cb	2																							
							s	1																							
6	3	2.0	4.0	60	45	2.0	q	3	1	4.0			12.0					4.0				B291909	100.58	102.11	0.182	PD/CA		VA05049846	1.53	3.9	
							cb	2																							
							s	1																							
																						B291910	STANDARD 7G		4.670	7G		VA05049846			
2	3	1.0	2.5	35	55	1.5	q	2	2	3.0			5.0					5.0	3.0			B291911	102.11	103.26	0.271			VA05049846	1.15	1.7	0.906
							s	1																							
							cb	2																							
0																						B291912	103.26	104.12	0.446			VA05049846	0.86	0.0	0.712
1	1	1.0	1.0	40		1.0	q	3	1	0.1			3.0					5.0	3.0			B291913	104.12	104.64	0.106			VA05049846	0.52	1.9	
3	3	1.0	3.0	60		20.0	q	1	3		0.1							2.0				B291914	104.64	105.80	0.169			VA05049846	1.16	2.6	
							lim	3																							
							s	2																							
							arg	4																							
1	1	1.5	1.5	45		10.0	arg	3	1		10.0										5.0	B291915	105.80	106.43	5.850		other is hematite	VA05049846	0.63	1.6	0.981
							chl	1																							
							s	4																							
							cb	2																							
																						B291916	BLANK		<0.005			VA05049846			
5	1	1.0	5.0	45		1.0	q	2		10.0								3.0				B291917	106.43	107.32	0.430			VA05049846	0.89	5.6	1.035
2	4	0.5	1.0	15	115	0.1	cb	5																							
0																						B291918	107.32	108.20	1.535			VA05049846	0.88	0.0	
3	1	1.5	2.0	70	60	5.0	q	3	4	5.0			5.0					5.0				B291919	108.20	109.73	0.308			VA05049846	1.53	2.0	0.983
							s	3																							
5	3	1.0	4.0	70		15.0	cb	3	4																						
							arg	3																							
2	1	1.0	1.6	70		15.0	q	1	3													B291920	109.73	110.35	0.061			VA05049846	0.62	3.2	1.13
							s	5																							
0																						B291921	110.35	111.05	0.129			VA05049846	0.70	0.0	
0																						B291922	110.35	111.05	0.187	DUP		VA05049846	0.70	0.0	
3	1	1.0	2.0	70			s	4	1				3.0									B291923	111.05	112.13	0.297			VA05049846	1.08	2.8	0.78
							chl	3																							
							arg	3																							
							cb	3																							
0																						B291924	112.13	112.78	0.234			VA05049846	0.65	0.0	
1	1	1.0	1.0	50			s	5					0.1									B291925	112.78	114.30	0.832			VA05049846	1.52	0.7	0.652
							chl	4																							
							arg	4																							
							cb	4																							
3	1	1.5	3.0	50	80		s	5			0.1							3.0				B291926	114.30	115.02	0.440			VA05049846	0.72	4.2	0.602
							chl	4																							
							arg	4																							
							cb	4																							

DRILL LOG LEGEND - P1 | DATE: 8 to 11-June-05 | PAGE 7 of 14

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.51	128.34	Clay to gravel texture. Colour is medium grey.	1	4	3	4	4	
10		128.34	129.43	Minor alt'd GND	1	2	1		1	
10		129.43	134.54	Unalt'd GND between sheeted qtz veins		1	1		1	
10		134.54	135.84	Sericitized GND zone. Central vein not visible. Zone begins/ends at ~45° to CA.		3	2		1	
10		135.84	145.19	Numerous qtz veins with ser/chl/cb altered selvages. Selvage dominates this section, to 90%.						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides									Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To							
0																						B291927	115.02	117.35	0.176			VA05049846	2.33	0.0	1.08
1	1	1.0	1.0	70			s	5														B291928	117.35	118.87	0.020			VA05049846	1.52	0.7	0.926
							chl	4																							
							arg	4																							
							cb	4																							
1	1	1.0	1.0	70			s	5														B291929	117.35	118.87	0.026	PD/CA		VA05049846	1.52	0.0	
							chl	4																							
							arg	4																							
							cb	4																							
																						B291930	STANDARD 4D		0.462	4D		VA05049846			
1	4	0.5	0.5	70			s	5														B291931	118.87	120.40	1.395			VA05049846	1.53	0.7	0.991
							chl	4																							
							arg	4																							
							cb	4																							
0																						B291932	120.40	121.16	0.268			VA05049846	0.76	0.0	0.742
0																						B291933	121.16	121.92	0.113			VA05049846	0.76	0.0	
2	1	2.0	3.0	80			s	5		10.0	2.0							4.0				B291934	121.92	123.44	1.415			VA05049846	1.52	1.3	1.245
							chl	4																							
							arg	4																							
							cb	4																							
1	6	0.5	0.5	70			s	5		20.0								4.0													
							chl	4																							
							arg	4																							
							cb	4																							
2	1	3.0	6.0	80			s	5		5.0	5.0							4.0				B291935	123.44	124.97	0.635			VA05049846	1.53	1.3	0.704
							chl	4																							
							arg	4																							
							cb	4																							
																						B291936	BLANK		<0.005			VA05049846			
																						B291937	124.97	125.51	0.172			VA05049846	0.54	0.0	1.155
0																						B291938	125.51	126.01	1.720			VA05049846	0.50	0.0	
0																						B291939	126.01	126.82	0.258			VA05049846	0.81	0.0	
0																						B291940	126.82	128.34	0.279			VA05049846	1.52	0.0	
2																						B291941	128.34	129.43	0.466			VA05049846	1.09	1.8	
																						B291942	128.34	129.43	1.155	DUP		VA05049846	1.09		
5	1	2.0	7.0	60		4.0	q	3	0		10.0		5.0					1.0	2.0			B291943	129.43	130.32	1.330			VA05049846	0.89	5.6	
							chl	2																							
							s	2																							
9	1	2.0	6.5	60		3.0	q	3	0		15.0	0.1	5.0					3.0	3.0			B291944	130.32	131.06	0.342			VA05049846	0.74	12.2	
							chl	2																							
							s	2																							
8	1	2.0	7.0	60		10.0	chl	3	0	5.0	8.0		3.0					3.0	3.0			B291945	131.06	132.59	0.309			VA05049846	1.53	5.2	
							s	3	0																							
							q	1																							
1	6	2.0	2.0	60		10.0	chl	3	0	5.0	30.0		10.0					4.0	2.0													
							s	3																							
							q	1																							
5	1	1.0	5.0	60		8.0	chl	3	0				10.0						3.0			B291946	132.59	134.11	1.040			VA05049846	1.52	3.3	
							s	2																							
1	1	1.0	1.0	65		0.0	q	3			3.0		2.0					1.0	3.0			B291947	134.11	134.54	0.033			VA05049846	0.43	2.3	
2	4	0.2	0.4	50		40.0	s	4			5.0		5.0					1.0	3.0			B291948	134.54	135.84	0.202			VA05049846	1.30	1.5	
							chl	2																							
							cb	2																							
2	4	0.2	0.4	50		40.0	s	4			5.0		5.0					1.0	3.0			B291949	134.54	135.84	0.163	PD/CA		VA05049846	1.30	0.0	
							chl	2																							
							cb	2																							
																						B291950	STANDARD 5E		1.525	5E		VA05049846			
3	1	3.5	6.0	50	65	4.0	s	4		5.0	5.0							3.0				B291951	135.84	136.84	0.242			VA05049846	1.00	3.0	
							chl	2																							
							cb	2																							
9	1	1.5	6.0	50		4.0	s	4		5.0	5.0		2.0					3.0	4.0			B291952	136.84	137.55	0.488			VA05049846	0.71	12.7	
							chl	2																							
							cb	2																							
6	1	2.0	7.0	45	70		s	4		2.0	2.0		1.0					3.0	0.0			B291953	137.50	138.68	0.396			VA05049846	1.18	5.1	
							chl	3																							
							cb	2																							
2	4	0.3	0.5	60			s	4		2.0	2.0		1.0					3.0	0.0													
							chl	3																							
							cb	2																							

DRILL LOG LEGEND - P1	DATE: 8 to 11-June-05	PAGE 9 of 14	
DRILL HOLE #: DG05-281C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				From 141.92 to 142.07m is one 15cm qtz vein w/ 3 lenses of massive sulphides 1-5mm wide.						
10		145.19	148.30	Unalt'd GND w/ qtz veins. Low angle veins have > sulphides		2	1		1	
10		148.30	150.88	Carb-rich GND. Fractures and matrix in-filled. Fractures trend to 40°/140°. Crumbly, weak texture.		3	3	1	3	
10		150.88	152.40	Unalt'd GND w/ qtz veins		2	1		1	
10		152.40	158.50	Carb-infused GND (as at 148.3-150.88m)		3	3	1	3	
				At 157.10-157.20m, gouge zone. Strong slickensides in sericite and ox'd pyrite on low-angle fracture.						
10		158.50	170.69	GND, unalt'd. Sheeted milky qtz veins		1	1		1	
				At 163.35: po/ser (50/50) zone 5x3cm.						

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To							
3	1	3.0	5.0	25	40		s	4		2.0								5.0				B291954	138.68	140.99	0.177			VA05049846	2.31	1.3	
							chl	4																							
							cb	3																							
2	4	0.5	1.0	45			s	3		5.0	5.0							2.0													
							chl	3																							
							cb	3																							
7	1	3.0	10.0	55		40.0	s	3		5.0			2.0					3.0				B291955	140.99	141.92	1.105			VA05049846	0.93	7.5	
							chl	3																							
							cb	3																							
																						B291956	BLANK		<0.005			VA05049846			
1	1	15.0	15.0	45		35.0	s	3		10.0			2.0					4.0				B291957	141.92	142.09	0.107			VA05049846	0.17	5.9	
							chl	3																							
							cb	3																							
6	3	2.0	2.0	50	40	10.0	s	3		5.0			3.0					3.0				B291958	142.09	143.26	1.315			VA05049846	1.17	5.1	
							chl	3																							
							cb	3																							
6	1	5.0	12.0	60	70	40.0	s	3		10.0	15.0							4.0				B291959	143.26	144.78	0.238			VA05049846	1.52	3.9	
							chl	3																							
							cb	3																							
2	1	3.0	5.0	70		20.0	s	3		10.0								4.0				B291960	144.78	145.19	1.530			VA05049846	0.41	4.9	
							chl	3																							
							cb	3																							
6	1	1.0	6.0	60	45	4.0	s	2		5.0	8.0		5.0					4.0	3.0			B291961	145.19	146.30	0.596			VA05049846	1.11	5.4	
							chl	1																							
							cb	1																							
6	1	1.0	6.0	60	45	4.0	s	2		5.0	8.0		5.0					4.0	3.0			B291962	145.19	146.30	0.816	DUP		VA05049846	1.11	5.4	
							chl	1																							
							cb	1																							
8	1	1.0	6.0	55	35	2.0	q	4			10.0	0.1	1.0					1.0	3.0			B291963	146.30	147.83	0.639			VA05049846	1.53	5.2	
							cb	2																							
3	3	0.5	1.5	60	50	1.0	q	4		2.0	5.0	5.0						3.0				B291964	147.83	148.30	6.340			VA05049846	0.47	6.4	
							cb	2																							
3	1	3.0	5.0	65		0.0							5.0						3.0			B291965	148.30	149.35	1.545			VA05049846	1.05	2.9	
8	3	3.0	8.0	65		1.0	cb	1					1.0						4.0			B291966	149.35	150.88	0.711			VA05049846	1.53	5.2	
							q	2																							
							chl	1																							
8	1	2.0	5.0	30	50	1.0	cb	1			2.0		5.0						3.0			B291967	150.88	152.40	0.285			VA05049846	1.52	5.3	
							q	2																							
							chl	1																							
4	1	2.0	5.0	40		2.0	q	4	0		5.0		1.0						5.0			B291968	152.40	153.92	0.627			VA05049846	1.52	2.6	
							cb	2																							
4	1	2.0	5.0	40		2.0	q	4	0		5.0		1.0						5.0			B291969	152.40	153.92	0.875	PD/CA		VA05049846	1.52	2.6	
							cb	2																							
																						B291970	STANDARD 2B		3.140	2B		VA05049846			
2	4	3.0	5.0	30		0.0																B291971	153.92	155.45	0.388			VA05049846	1.53	1.3	
1	3	1.0	1.0	30		4.0	q	4	0	0.1																					
							chl	3	0																							
6	1	2.0	6.0	30	55	2.0	q	3	0		2.0							1.0				B291972	155.45	156.97	0.364			VA05049846	1.52	3.9	
							chl	3																							
2	1	3.0	4.0	50		2.0	q	1	0	1.0			10.0					3.0	3.0			B291973	156.97	158.50	0.170			VA05049846	1.53	1.3	
							s	2																							
							chl	2																							
7	1	1.2	5.5	50		2.0	q	3		3.0			5.0						5.0			B291974	158.50	160.02	0.099			VA05049846	1.52	4.6	
							s	1																							
							chl	1																							
9	1	1.0	4.0	50		1.0	q	3			5.0							1.0				B291975	160.02	161.54	0.241			VA05049846	1.52	5.9	
							s	1																							
							chl	1																							
																						B291976	BLANK		<0.005			VA05049846			
11	1	3.0	10.0	50		4.0	q	3			10.0							1.0				B291977	161.54	163.07	1.770			VA05049846	1.53	7.2	
							s	1																							
							chl	2																							
3	1	1.0	2.0	50		2.0	q	3			10.0							1.0				B291978	163.07	164.59	0.353			VA05049846	1.52	2.0	
							s	1																							
							chl	2																							

DRILL LOG LEGEND P1 | DATE: 8 to 11-June-05 | PAGE 11 of 14

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		170.69	173.74	Carb-rich zone again. Crumbly GND.		1	2		2	
10		173.74	178.31	Unalt'd GND w/ milky white qtz veins		2	1		1	
10		178.31	181.36	Slightly more carb on microfractures and throughout, appears as veinlets in random orientations		2	1		2	
10		181.36	184.90	Minor silicified GND (qtz milky, boundaries gradational). Calcite on microfractures/irregular veinlets.		1	1		1	
10		184.90	185.24	One qtz vein w/ big selvage		3	3			
10		185.24	189.53	Unalt'd GND. Chl section at 189.45m						
10		189.53	191.12	Shear zone. GND gains fabric (foliation) to 80°.	2	2	2	1	1	
10		191.12	192.55	Unalt'd GND w/ qtz veins						
10		192.55	194.40	Qtz and carb veins w/in heavily chloritized zone		2	4		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

PAGE 12 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS							Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval							
											Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2		Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
7	1	1.0	5.0	45			2.0	q	2			10.0							1.0				B291979	164.59	166.12	**1.150**			VA05049846	1.53	4.6	
								s	1																						
								chl	1																						
4	1	1.0	4.0	50			2.0	q	2			5.0											B291980	166.12	167.64	**0.407**			VA05049846	1.52	2.6	
								s	1																						
								chl	1																						
6	1	1.5	5.0	45			1.0	q	2			15.0		3.0									B291981	167.64	169.16	**0.853**			VA05049846	1.52	3.9	
								s	1																						
								chl	1																						
6	1	1.5	5.0	45			1.0	q	2			15.0		3.0									B291982	167.64	169.16	**0.083**	DUP		VA05049846	1.52	3.9	
								s	1																						
								chl	1																						
9	1	1.5	5.0	50			6.0	q	2		5.0	5.0		0.1					3.0	5.0			B291983	169.16	170.69	**1.170**			VA05049846	1.53	5.9	
								s	1																						
								chl	1																						
9	1	1.0	6.0	50			1.0	q	2		2.0	2.0							1.0				B291984	170.69	172.21	**0.280**			VA05049846	1.52	5.9	
								s	1																						
								chl	1																						
3	4	0.8	2.0	15			0.0				0.0																					
9	1	2.0	11.0	50			3.0	q	2			5.0		0.1						2.0			B291985	172.21	173.74	**0.237**			VA05049846	1.53	5.9	
								s	1																						
								chl	1																						
7	1	3.0	10.0	40			2.0	q	3	0		5.0		0.1						5.0			B291986	173.74	175.26	**0.963**			VA05049846	1.52	4.6	
								chl	2																						
								cb	1																						
7	1	4.0	9.0	50			1.0	q	3			5.0		1.0						4.0			B291987	175.26	176.78	**0.176**			VA05049846	1.52	4.6	
								chl	2																						
								cb	1																						
6	1	5.5	10.0	50	40		2.0	q	3			5.0		1.0						0.0			B291988	176.78	178.31	**0.232**			VA05049846	1.53	3.9	
								chl	2																						
								cb	1																						
6	1	5.5	10.0	50	40		2.0	q	3			5.0		1.0						0.0			B291989	176.78	178.31	**0.254**	PD/CA		VA05049846	1.53	0.0	
								chl	2																						
								cb	1																						
																							B291990	STANDARD 4D		**0.453**	4D		VA05049846			
7	1	1.2	7.2	70			2.0	q	3			5.0											B291991	178.31	179.83	**1.810**			VA05049846	1.52	4.6	
								s	3																						
3	1	2.0	2.0	50			2.0	q	3			5.0		3.0						4.0			B291992	179.83	181.36	**0.237**			VA05049846	1.53	2.0	
								s	3																						
								cb	2																						
5	1	1.0	5.0	50			2.0	q	3			5.0		1.0						4.0			B291993	181.36	182.88	**0.069**			VA05049846	1.52	3.3	
								s	3																						
								cb	2																						
																							B291994	182.88	184.40	**0.037**			VA05049846	1.52	0.0	
5	1	1.5	3.5	40			2.0	q	3		3.0			3.0						3.0			B291995	184.40	184.90	**0.087**			VA05049846	0.50	10.0	
								chl	1																						
																							B291996	BLANK		**<0.005**			VA05049846			
1	1	2.0	2.0	50			23.0	q	2		10.0			3.0					2.0	3.0			B291997	184.90	185.24	**1.130**			VA05049846	0.34	2.9	
								chl	4																						
2	1	1.0	2.0	50			0.2	q	2			5.0							1.0				B291998	185.24	185.93	**0.044**			VA05049846	0.69	2.9	
0																							B291999	185.93	187.45	**0.024**			VA05049846	1.52	0.0	
3	1	1.0	3.0	50			1.0	q	4	0	1.0			1.0					2.0	3.0			B292000	187.45	188.98	**0.019**			VA05049846	1.53	2.0	
								chl	2																						
								s	2																						
0																							B292001	188.98	189.53	**0.022**			VA05049846	0.55	0.0	
0																							B292002	188.98	189.53	**0.020**	DUP		VA05049846	0.55	0.0	
2	6	1.0	2.0	70			0.0				40.0								5.0				B292003	189.53	190.50	**0.055**			VA05049846	0.97	2.1	
4	6	1.0	3.0	70			0.0				40.0								5.0				B292004	190.50	191.12	**0.192**			VA05049846	0.62	6.5	
4	1	1.0	4.0	50								3.0											B292005	191.12	192.55	**0.154**			VA05049846	1.43	2.8	
3	1	2.0	3.5	40			328	chl	4		15.0	2.0		1.0					5.0	5.0			B292006	192.55	193.55	**0.177**			VA05049846	1.00	3.0	
								q	2																						
								cb	2																						
1	4	1.5	1.5	40																								selvage for both vein types				
1	6	1.0	1.0	50				chl	4		98.0			2.0									B292007	193.55	194.40	**0.366**			VA05049846	0.85	1.2	
								q	2																						
								cb	2																						

DRILL LOG LEGEND - P1 | DATE: 8 to 11-June-05 | PAGE 13 of 14

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		194.40	199.17	Unalt'd GND and qtz veins w/ selvages. At 194.7m, a xenolith of amphibolite, 5x4cm. Slickensides shown in chl/ser on fracture face 20° to CA. Qtz veins are mostly milky qtz on margins and selvage with cloudy grey qtz in centre.	1	2	1		1	
10		199.17	200.85	Carbonate-infused GND. Breaks along veins at 25°-35°. Regular fractures (no carb) at 65° to CA. Veins (noted), are somewhat silicified and difficult to see. Slickensides on 60° fract face, perpendicular (drawn) to CA.		2			2	
10		200.85	202.09	Unalt'd GND except selvage around qtz veins and sulphide vein. 3cm gouge zone at 201.61m		2		1	1	
10		202.09	204.72	V. fine grained GND. Colour is dark grey. Aphanitic, competent texture.			1			
10		204.72	222.50	Unalt'd GND. From 214.88 to 216.35m. Rich in carbonate veining on fractures. GND is 35% qtz, 25% bt, 20% feldsp, 20% hb. (E.O.H)		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
6	1	1.0	4.0	35	120	2.0	q	2	0	1.0								5.0				B292008	194.40	195.07	**0.060**			VA05049846	0.67	9.0	
							s	2																							
6	1	1.0	4.0	35	120	2.0	q	2	0	1.0								5.0				B292009	194.40	195.07	**0.059**	PD/CA		VA05049846	0.67	9.0	
							s	2																							
																						B292010	STANDARD 6F		**2.880**	6F		VA05049846			
11	1	1.0	7.0	40	55	1.0	q	3		0.1	0.1		1.0						3.0			B292011	195.07	196.60	**0.043**			VA05049846	1.53	7.2	
							s	1																							
10	1	0.8	3.0	35	65	2.0	q	3		1.0	6.0		0.1					2.0	2.0			B292012	196.60	198.12	**0.192**			VA05049846	1.52	6.6	
							s	1																							
3	1	1.5	2.5	45		2.0	q	3		1.0	6.0		0.1					2.0	2.0			B292013	198.12	199.17	**0.118**			VA05049846	1.05	2.9	
							s	1																							
2	6	1.2	1.6	30		0.0				100								4.0													
5	1	1.0	5.0	60		2.0	q	3	0	3.0	0.1							4.0				B292014	199.17	200.85	**0.400**			VA05049846	1.68	3.0	
3	1	0.5	1.5	60		4.0	q	3	0	5.0	1.0							4.0				B292015	200.85	202.09	**0.558**			VA05049846	1.24	2.4	
1	6	0.5	0.5	60		10.0	q	4		30.0								4.0													
							chl	2																							
																						B292016	BLANK		**<0.005**			VA05049846			
4	1	1.3	3.5	45		3.0	q	4		3.0	0.1		0.1					4.0	3.0			B292017	202.09	203.45	**0.485**			VA05049846	1.36	2.9	
							chl	1																							
5	1	1.5	2.3	60	35	2.0	q	3	0	3.0			5.0						4.0			B292018	203.45	204.72	**0.399**			VA05049846	1.27	3.9	
1	6	0.4	0.4	45		3.0	q	4	0	40.0	40.0		10.0					3.0	4.0												
5	1	1.0	4.0	50		3.0	q	3	0		5.0							2.0				B292019	204.74	205.74	**0.561**			VA05049846	1.00	5.0	
5	1	1.0	4.0	45	60	0.0				10.0	3.0							3.0				B292020	205.74	207.26	**0.269**			VA05049846	1.52	3.3	
3	4	1.0	1.4	30		0.5	cb	1		0.0																					
7	1	1.0	5.0	55		1.0	q	3		0.1			0.1					4.0	4.0			B292021	207.26	208.79	**0.276**			VA05049846	1.53	4.6	
7	1	1.0	5.0	55		1.0	q	3		0.1			0.1					4.0	4.0			B292022	207.26	208.79	**0.255**	DUP		VA05049846	1.53	4.6	
8	1	1.0	7.0	40	55	1.0	q	4			5.0		5.0					4.0	4.0			B292023	208.79	210.31	**0.109**			VA05049846	1.52	5.3	
5	1	1.0	3.0	40	60	0.5	q	2			1.0		2.0					3.0	2.0			B292024	210.31	211.84	**0.199**			VA05049846	1.53	3.3	
2	1	0.5	1.0	60							2.0											B292025	211.84	213.36	**0.023**			VA05049846	1.52	1.3	
2	4	0.5	1.0	15		0.0				0.0																					
																						B292026	213.36	214.88	**0.157**			VA05049846	1.52	0.0	
1	1	1.0	1.0	55		0.5	q	3	0	5.0								4.0				B292027	214.88	216.41	**0.051**			VA05049846	1.53	0.7	
1	4	0.4	0.4	15		0.0				0.0																					
4	1	0.5	2.0	30	50	1.0	q	3	0		5.0		5.0					4.0	4.0			B292028	216.41	217.93	**0.016**			VA05049846	1.52	2.6	
							chl	1																							
4	1	0.5	2.0	30	50	1.0	q	3	0		5.0		5.0					4.0	4.0			B292029	216.41	217.93	**0.015**	PD/CA		VA05049846	1.52	2.6	
							chl	1																							
																						B292030	STANDARD 5E		**1.450**	5E		VA05049846			
3	1	1.5	3.0	50		1.0	q	3	0		4.0		5.0					2.0	4.0			B292031	217.93	219.46	**0.055**			VA05049846	1.53	2.0	
4	1	1.5	4.5	60	45	1.0	q	3	0	2.0	7.0		3.0					3.0	4.0			B292032	219.46	220.98	**0.403**			VA05049846	1.52	2.6	
7	1	1.0	5.0	50						2.0	10.0		2.0					3.0	4.0			B292033	220.98	222.50	**0.186**			VA05049846	1.52	4.6	
																								E.O.H.							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-282C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:

BEARING: 000 | DIP: -50°

DATE STARTED: 10-June-05 (7:00 PM) | DATE COMPLETED: 15-Jun-05

LOGGED BY: Kristian Whitehead & Dave Hladky

COORD SYSTEM: NAD 27: EASTING: 459104 NORTHING: 7099244

COORD SYSTEM: NAD 83: EASTING: 458985 NORTHING: 7099428

NAD 27 (CORRECTED for historic grid): EASTING: 459074 NORTHING: 7099254

SECTION LINE(historic grid) = 459075 E

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing:

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
6.10	191.80	GND
191.80	218.67	MSED
218.67	221.62	GND
221.62	237.80	MSED
237.80	240.53	GND
240.53	251.46	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B292708 - B292923

Requisition #: MASP448STRGOL.05Q | Date Shipped: 17-June-05

Lab Record #: VA05049598 | Date Received: 4-July-05

Sample Sequence: B292924 - B292979

Requisition #: MASP448STRGOL.05Q | Date Shipped: 21-June-05

Lab Record #: VA05052041 | Date Received: 11-July-05

Duplicates:	B292722, B292742, B292762, B292782, B292802, B292842, B292862, B292882, B292902, B292922, B292942, B292962
Preparation Duplicate/ Check Assay:	B292709, B292729, B292749, B292769, B292789, B292809, B292829, B292849, B292869, B292889, B292909, B292929, B292949, B292969
Standards:	B292710, B292730, B292750, B292770, B292790, B292810, B292830, B292850, B292870, B292890, B292910, B292930, B292950, B292970
Blanks:	B292716, B292736, B292756, B292776, B292796, B292816, B292836, B292856, B292876, B292896, B292916, B292936, B292956, B292976

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
100.0	337.7	51.4	003.7	004.7
175.0	336.9	51.7	002.9	003.9
250.0	336.1	52.7	002.1	003.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 14-17, 2005	PAGE 1 of 18	
DRILL HOLE # : **DG05-282C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		0.00	6.10	Casing (recovered 5.73-6.10m), GND description below.						
10	6.10-191.80	6.10	14.30	GND description as previous 2005 holes. sheeted vning essentially begins @ collar depth, vns are regularly @ ~40-45° to CA w/ avg widths of 0.25-1cm w/ dissem aspy (~trace to 3%) common. Vn spacing is currently @ 5-40cm apart. Fractures have limonite staining, lim is not pervasive.						
10		14.30	30.79	Core recovery is poor & core is severely broken, vning w/in coherent, larger pieces is not striking but subtle in appearance. Broken pieces don't have qtz pieces w/in, indicating veining. Thus conclusion remains @ modest vning system.						
10		30.79	35.05	Core remains the same GND mineralogy as from casing. Vning abundance is up to ~10-15/metre, but broken core makes precision of #'s difficult. Primary angle is 40° to CA w/ aspy the predominant sulphide w/in qtz vns.						
10		35.05	36.73							
10		36.73	37.17	Core is alt to light grey, mafic free, qtz eyes, sericite & chlorite present a soft, essentially a selvage for a vn, defined by ox'd sulphides & unox'd aspy ~5% & py ~1-2%. the interpreted angle to CA is @ 40° to CA. Some carb vnlets & clay.	2	3	2	2	1	
10		37.17	39.78							
10		39.78	39.86	Sandy/clay seam (unit). Core appears mildly bleached some (trace) aspy flecks.		1		2		
10		39.86	44.00	At ~42.43m is an area of GND pc's w/ a large amount of aspy & py. Orientation imperceptible but core pc's appear somewhat alt'd. Sulphides mildly ox'd: py @ ~3-5%, aspy @ 3%, difficult to be sure.		2	1	1	2	
10		44.00	44.20	Med alt'n zone due to two 1 & 1.5cm qtz & qtz/carb vns w/ ~5-10% sulphides (aspy & py). Chlorite hue on core. Core mafic devoid. Dull green/grey.	1	2	2		1	
10		44.20	53.34							

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides										Oxidation						Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA05048596 Return Samples
7	1	0.5	3.0	40	45								0.1									B292708	6.10	7.62	0.088			VA05049598	1.52	
7	1	0.5	3.0	40	45								0.1									B292709	6.10	7.62	0.096	PD/CA		VA05049598	1.52	
																						B292710	STANDARD 3C		0.093	3C		VA05049598		
9	1	1.8	6.3	40									0.1/2									B292711	7.62	9.14	0.124			VA05049598	1.52	
7	1	1.0	3.5	40									0.1/5									B292712	9.14	10.67	0.283			VA05049598	1.53	
3	1	1.0	2.5	35	40								0.1/3									B292713	10.67	12.19	0.205			VA05049598	1.52	
4	1	0.5	2.8	35	40								0.1									B292714	12.19	13.72	0.077			VA05049598	1.53	
2	1	0.3	0.3	20																		B292715	13.72	15.29	0.050			VA05049598	1.57	
																						B292716	BLANK		<0.006			VA05049598		
2	1	0.3	0.3	40									0.1									B292717	15.29	16.76	0.065			VA05049598	1.47	0.231
3	1	0.3	0.6	35	40								0.1									B292718	16.76	18.29	0.064			VA05049598	1.53	
7	1	0.5	4.0	35	40								0.1									B292719	18.29	19.81	0.081			VA05049598	1.52	
4	1	0.5	0.8	35									2.0									B292720	19.81	21.34	0.117			VA05049598	1.53	
6	1	1.0	4.0	35									0.1									B292721	21.34	22.86	0.122			VA05049598	1.52	
1	4	0.3	0.3	40																											
6	1	1.0	4.0	35									0.1									B292722	21.34	22.86	0.133	DUP		VA05049598	1.52	
1	4	0.3	0.3	40																											
3	1	0.3	2.0	30									0.1									B292723	22.86	24.38	0.195			VA05049598	1.52	
8	1	0.3		30	40								1.0									B292724	24.38	25.91	0.137			VA05049598	1.53	
													1.0									B292725	25.91	27.48	0.193			VA05049598	1.57	
													1.0									B292726	27.48	28.96	0.112			VA05049598	1.48	
8	1	0.8	0.8	40									1.0									B292727	28.96	30.48	0.110			VA05049598	1.52	
10	1	0.8	3.5	40									3.0									B292728	30.48	32.00	0.126			VA05049598	1.52	0.218
10	1	0.8	3.5	40									3.0									B292729	30.48	32.00	0.123	PD/CA		VA05049598	1.52	
																						B292730	STANDARD 4D		0.424	4D		VA05049598		
15	1	1.0	6.0	40									0.1									B292731	32.00	33.53	0.169			VA05049598	1.53	0.231
4	1	0.5	1.8	30	40								0.1									B292732	33.53	35.05	0.182			VA05049598	1.52	0.206
5	1	0.3	2.5	35	40								0.1									B292733	35.05	36.58	0.078			VA05049598	1.53	0.192
				40		44	3			2.0			2.0									B292734	36.58	37.68	0.211			VA05049598	1.10	0.269
6	1	0.5	4.0	35	40								1.0									B292735	37.68	39.62	0.106			VA05049598	1.94	0.226
																						B292736	BLANK		<0.006			VA05049598		
																						B292737	39.62	41.15	0.056			VA05049598	1.53	0.19
4	1	0.5	2.6	30	45	10.2				3.0			3.0									B292738	41.15	42.67	0.187			VA05049598	1.52	0.189
8	1	1.0	4.6	40		22	2	1		1.0			1.0									B292739	42.67	44.20	0.288			VA05049598	1.53	0.203
1	3	1.5	1.5	60	65	22	2	1		0.1			6.5																		
9	1	0.5	4.5	35	60					1.0			2.0									B292740	44.20	45.72	0.096			VA05049598	1.52	
4	1	0.3	2.0	33	68					0.1			0.1									B292741	45.72	47.24	0.033			VA05049598	1.52	
4	1	0.3	2.0	33	68					0.1			0.1									B292742	45.72	47.24	0.030	DUP		VA05049598	1.52	
																						B292743	47.24	48.77	0.024			VA05049598	1.53	
													0.1					2.0				B292744	48.77	50.29	0.136			VA05049598	1.52	
																						B292745	50.29	51.82	0.084			VA05049598	1.53	
6	1	0.3	1.3	40						0.1			0.1					4.0				B292746	51.82	53.34	0.070			VA05049598	1.52	

DRILL LOG LEGEND - P1	DATE: June 14-17, 2005	PAGE 3 of 18	
DRILL HOLE # : **DG05-282C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		53.34	53.81	Intense alt'n zone, core is extremely bleached & reduced almost to clay ox'd py & aspy. Focus appears to be @ 53.42-53.47m where there's a digested carb/qtz vn @ 55-60° to CA. Sulphides are all concentrated w/in or predominantly adjacent, thus a large selvage from 53.34-53.81m.	2	4	2	3	3	
10		53.81	56.23	Core is salt & pepper textured; feldspars are reduced to white sericite & hornblendes remain as mafics. Core is like a strong clay.	1	4	1	3	1	
10		56.23	56.55							
10		56.55	57.34	Slickenside @ 10° to CA w/ gouge on one of slickenside surfaces. Srfc had ox'd aspy, perhaps py w/ slickened srfc.						
10		57.34	57.73							
10		57.73	57.91	Core becomes severely hydro alt'n etched yet mafics remain as salt/pepper texture. Qtz/carbs are broken to chalk-like hardness. Ox'd aspy & py present as graphite grey stringers/vns.		3	1	2	3	
10		57.91	58.79							
10		58.79	59.44	Slightly chlorite/sericite alt zone, essentially a continuous selvage section due to sheeted vning closeness.		2	2		1	
10		59.44	61.79							
10		61.79	63.40	Extreme hydrothermal alt'n window, core is v. bleached, yet some mafic zones exist. sericite & chlorite abundant, ox sulphides are visible abundant in zones, mostly looks aspy. v. broken core makes interpretation difficult. carbs abundant due to acid testing response. sulphides may be ~2-4% of core.		4	2	2	3	
10		63.40	66.50							
10		66.50	67.30	Selvage alt'd around gouge zone @ 67.06-67.14m. Gouge has ~1% py & >1% aspy. Gouge fizzes on acid, and is grey & white. Contact of gouge @ ~60-65° to CA.		4	2	5	2	
10		67.30	71.63	Core is v. broken but long shards along carb vnlets & stringers. Core is abundant on fracs w/ calcite & dolomite. Opinion is the predominant sulphides are coming in w/ carbs w/ py being the most noticed associated w/ carb vning. Carbs are often sheared w/ frac rock @ lower angles to CA.						
10		70.05	82.69	Core is v. broken, v. high amount of pc's w/ slickensides of polished aspy & py, which is mostly ox'd. Frac angles include 30° & 55° to CA.						
10		73.43	73.54	Faulted gouge/sand sized gravel w/ pure qtz pc's/slickensided pc's. Angle looks to be @ 20° to CA w/ ox'd aspy & py. Carb pc's also involved.		1		2	2	
10		74.18	75.48	Alteration zone, core is essentially a connected set of selvages. The focus of the selvages would be an 11cm thick carb dominant sulphide & minor qtz vn @ 35-40° to CA. Py continues to be dominant sulphide running w/ carb vns.		2	2		1	
				At 77.10m: the qtz vns have increased in size to 1cm or greater, and the first appearance of po (0.1%).						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS									% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides									Oxidation					Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048696 Return Samples
7	1	4.0	8.3	50	55					5.0			10.0					4.5				B292747	53.34	54.86	0.343		max aspy content	VA05049598	1.52	
4	1	1.3	3.6	55	60	24				5.0			20.0					3.0				B292748	54.86	55.56	0.420		max py	VA05049598	0.70	
4	1	1.3	3.6	55	60	24				5.0			20.0					3.0				B292749	54.86	55.56	0.422	PD/CA	max py	VA05049598	0.70	
																						B292750	STANDARD 1A		0.900	1A		VA05049598		
										0.1			0.1					4.5				B292751	55.56	56.39	0.264			VA05049598	0.83	
7	1	0.5	3.5	40	45	95	2.5		1	30			30.0									B292752	56.39	57.34	0.304			VA05049598	0.95	
2	1,3	0.3	0.5	45		12	2			2.0			50.0					4.5				B292753	57.34	57.91	0.221			VA05049598	0.57	
10	3	1.5	6.5	45		14	2			1.0			20.0									B292754	57.91	59.44	0.274			VA05049598	1.53	
6	3,1	0.5	2.3	40	45					0.1			1.0									B292755	59.44	60.96	0.150			VA05049598	1.52	
																						B292756	BLANK		<0.005			VA05049598		
6	1	0.5	4.3	40	45	1.5	1			1.0			5.0									B292757	60.96	61.79	0.171			VA05049598	0.83	
										1.0			3.0					4.5				B292758	61.79	62.11	0.164			VA05049598	0.32	
	3									0.1			2.0					4.5				B292759	62.11	62.48	0.159			VA05049598	0.37	
	3									2.0			2.0									B292760	62.48	63.40	0.175			VA05049598	0.92	
5	1	0.5	2.0	40	45								0.1									B292761	63.40	64.01	0.036			VA05049598	0.61	
5	1	0.5	2.0	40	45								0.1									B292762	63.40	64.01	0.052	DUP		VA05049598	0.61	
6	1	0.5	2.3	40	45					1.0			1.0									B292763	64.01	65.53	0.102			VA05049598	1.52	
2	4	0.3	0.5	40	20								5.0																	
2	4	0.1	0.3	30	40																	B292764	65.53	66.50	0.026			VA05049598	0.97	
																						B292765	66.50	67.30	0.199			VA05049598	0.80	
9	1	1.0	4.3	40									0.1									B292766	67.30	68.58	0.090			VA05049598	1.28	
6	1	0.8	2.5	50	60								0.1									B292767	68.58	70.10	0.136			VA05049598	1.52	
										0.5			0.5									B292768	70.10	71.63	0.092			VA05049598	1.53	
										0.5			0.5									B292769	70.10	71.63	0.090	PD/CA		VA05049598	1.53	
																						B292770	STANDARD 5E		1.545	5E		VA05049598		
5	1	0.5	3.5	35									0.5									B292771	71.63	73.16	0.070			VA05049598	1.53	
3	1	0.8	2.5	40									0.1									B292772	73.16	74.18	0.074			VA05049598	1.02	
1	3	11.0	11.0	45		50				6.5			1.0									B292773	74.18	74.68	0.355			VA05049598	0.50	
5	1	1.0	3.0	40	50	20	1.5			1.0			2.0									B292774	74.68	76.20	0.114			VA05049598	1.52	
1	4	0.8	0.8	50		20	1.5			40			0.5														broken to bits			
6	1	1.3	4.3	40	50	22	1.5			1.0			0.7									B292775	76.20	77.72	0.126		broken to bits	VA05049598	1.52	
																						B292776	BLANK				broken to bits	VA05049598		
6	1	3.0	8.8	50		10	1				0.1		0.1									B292777	77.72	79.25	0.066			VA05049598	1.53	
5	1	1.0	3.8	30		9	2		1		0.1											B292778	79.25	80.77	0.038		v. broken	VA05049598	1.52	
																						B292779	80.77	82.30	0.060			VA05049598	1.53	

DRILL LOG LEGEND - P1	DATE: June 14-17, 2006	PAGE 5 of 18		
DRILL HOLE # : DG05-282C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		82.94	83.24	Highly alt'd clay ream, sericite prevalent. White-grey clay, contact @ 82.94m @ 40° to CA, contact @ 83.24m @ 60°, slickenside srfc on either contact w/ competent core. Visible ox'd sulphide vnlets @ ~60° to CA.						
				At 83.24m: salt & pepper bleached/alt'd GND begins from this point. Core appears as acid bleached. Core is coherent, can be mushed by pushing heavy on it, indicating substantial sericite/clay content. Frac srfc's are commonly coated w/ slickensided ox'd sulphides.	2	4	1	2	4	
10		85.34	85.90	Core is very broken yet ox'd sulphides are abundant on fracs & fracs are abundantly slickensided. Py & aspy are discernable in some places.						
10		85.90	86.87	Alt'n selvage w/ slickensides on fracs w/ ox'd sulphide staining on srfc @ ~50° to CA.	2	3	2	1	0	
10		87.67	88.00	Same as above.	2	3	2	1	1	
10		91.44	93.19	Same as above w/ carb stringers on occasion. ~1% of core.	2	3	2	1	1	
10		93.52	94.01	Alt'n selvages contiguous due to qtz & carb vns @ ~60° to CA.	2	3	2	1	1	
10		95.63	96.01	Same as above.	2	3	2	1	1	
10		96.01	99.06	GND; mod to strong ser+ arg alt'n, locally wkly sheared to fault gg		3		4	2	
				At 97.86 - 97.87m = 0.5 cm py + aspy vn + qtz + cb						
				A few 1-2 cm dark mafic "xenos", commonly biotite (70%) + feld (+/- chl)						
				Tr aspy in selvages, disseminated						
				Local graphitic-pyritic slip surfaces at 60 deg						
10		99.06	100.58	Similar to above; slightly more sulphide veining		3		4	2	
				99.06 - 99.07m; qtz-cb vn @ 10 deg with 4% aspy + 0.3 cm qtz aspy vnlt (+/-cb) at 55 deg						
				At 99.2 m - graphic slip at 10 deg						
				At 99.53 - 99.57m, gougy zone (flt'd) at 30 deg to CA						
				Includes a 1 cm (99.54 - 99.55m) py-aspy +/- qtz vn						
				Commonly sheared to fract'd at 10-20 deg; highly alt'd, minor less alt'd GND zone						
				At 99.96 - 99.98m; similar py+/- py-aspy+/- qtz cb vn as abv; also with flt gg at 90 deg and at 20 deg to vn (at 70 deg)						
				At 100m fractured/sheared foliation at 60 deg and 20 deg						
10		100.58	102.11	As above; weakly sheared at 10-20 deg		2		3	2	
				At 105.73 - 105.74m = py + aspy + qtz/cb vn at 70 deg with a graphitic slip surface; possibly syngenetic/fracture filling; dominantly py on one side and aspy on other						
				At 101.2m fracture foliation at 10 deg to CA						
				At 101.96 to 101.97m = 1 cm fault gouge at 10 deg						
10		102.11	103.63	At 102.25m = fracture foliation at 20 deg and 120 deg		3		4	2	
				At 102.75m gougy surface (possibly shear - wk faulting) at 20 deg						
				At 102.75m slip surfaces (10cm spacing commonly) at 160 deg (relative to previous slip)						
				At 103.5m = fracture foliation at 5 deg; cb coated						
10		103.63	104.37	Moderate to strong alteration with shear in upper 20 cm		2		2	1	
				At 103.9m shear fractures at 20 degrees						
				At 103.95m fracture foliation at 60 deg (150 deg)						
				At 104.2m pyritic slip surface at 60 deg (150 deg)						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA0504696 Return Samples
																						B292780	82.30	83.82	**0.121**			VA05049598	1.52	
3	1	1.0	1.6	45	50	1.52							2.0									B292781	83.82	85.34	**0.066**			VA05049598	1.52	
3	1	1.0	1.6	45	50	1.52							2.0									B292782	83.82	85.34	**0.107**	DUP	v. broken, poor recovery, pc's only	VA05049598	1.52	
2	1	1.5	2.5	70	75	1.52							3.0									B292783	85.34	86.87	**0.352**		v. broken, poor recovery, pc's only	VA05049598	1.53	
3	1	0.1	0.3	60	70	0.5	1						0.1									B292784	86.87	87.67	**0.062**			VA05049598	0.80	0.162
4	1	1.5	2.8	50						0.1			0.1		0.1							B292785	87.67	88.00	**0.144**			VA05049598	0.33	
1	4	0.3	0.3	50									0.1		0.1															
3	1	0.3	0.8	50	55					0.1			0.1									B292786	88.00	88.39	**0.371**			VA05049598	0.39	0.208
																						B292787	88.39	91.44	**0.062**			VA05049598	3.05	0.282
8	1	1.0	3.8	50		1.5	2			0.1			1.0									B292788	91.44	92.96	**0.175**			VA05049598	1.52	0.243
8	1	1.0	3.8	50		1.5	2			0.1			1.0									B292789	91.44	92.96	**0.180**	PD/CA	too altered to see	VA05049598	1.52	
																						B292790	STANDARD 2B		**3.280**	2B		VA05049598		
5	1	1.0	4.0	60		18	2						0.1									B292791	92.96	94.17	**0.161**			VA05049598	1.21	0.123
3	4	0.8	1.5	60		16	3	2		0.1			0.1																	
1	1	0.8	0.8	50									0.5									B292792	94.17	95.63	**0.084**		core is too broken	VA05049598	1.46	0.173
1	3	2.0	2.0	50		37	3.5	2		2.0			2.0									B292793	95.63	96.01	**0.175**			VA05049598	0.38	
3	3	0.3	0.8	40	45								0.1									B292794	96.01	97.54	**0.074**			VA05049598	1.53	0.339
1	6	0.1	0.1	60		9.0	2			2.0			2.0																	
4	3	0.3	3.0	45		2.0	s,cb,arg	3		5.0			4.0																	
1	6	0.5	1.0	45		1.0	cb	4	0	30.0			5.0									B292795	97.54	99.06	**0.236**		0.5 cm py + aspy vnlt; qtz/cb/ +/- py & aspy vnlts	VA05049598	1.52	0.501
																						B292796	BLANK		**<0.005**			VA05049598		
4	6	2.0	4.0	45	60	2.0	q,cb,arg	3	0	5.0			3.0									B292797	99.06	100.58	**0.347**			VA05049598	1.52	0.395
1	3	1.0	1.0	10		0.5	q,cb,arg	2	0				4.0																	
2	6	1.0	1.5	70		3.0	3	4	1	40.0			5.0										(99.54	99.55)			py/aspy qtz-cb vn			
2	6	2.0	2.0	70		2.0	3	4	1	45.0			5.0										(99.96	99.98)			py/aspy + qtz/cb vn			
4	3	0.8	4.0	60	50	3.0	3	4	0	3.0			2.0									B292798	100.58	102.11	**0.231**		0.5% diss aspy	VA05049598	1.53	0.449
1	6	0.5	0.5	70		2.0	3	3	0	45.0			30.0										(105.73	105.74)						
2	3	0.3	2.0	50	45	3.0	q/cb/arg	4	0	2.0			0.5									B292799	102.11	103.63	**0.048**			VA05049598	1.52	0.417
2	3	1.0	3.0	60	45	3.0	q/cb/arg	3	0	3.0			0.5									B292800	103.63	104.37	**0.064**			VA05049598	0.74	0.233

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
10		104.37	105.60	GND; less alt'd; less shr; common 1-2mm qtz-py-aspy-cb vnlts at 60 deg		2		1	1		4
10		105.60	106.68	Highly alt'd GND; possibly shear/fault zone at 105.65 to 105.7m; 105.7 to 105.8m highly altered with moderate shear at 45 deg; At 105.6 -105.65m py+aspy+qtz/cb veins (2 to 3) up to 1cm in hanging wall of high alteration/ shear zone; lower contact to this zone at 106.2m at 45 deg		3		5	2		
10		106.68	107.20	As above		3		5	2		
10		107.20	108.20	Moderately altered GND; trace disseminated py in selvages; At 107.6m = slip face at 60 deg to core axis		2		2	1		
				At 107.9 - 108.0m gougy zone, possibly a flt; high argillite alt'n with tr-1% diss py; upper contact at 70 deg; common slip faces at 60 deg							
10		108.20	109.72	Moderately alt'd GND; wk shr fracturing; at 108.25m shear foliation at 60 deg; increasingly alt'd towards the base; more rubbly		2		2	2		
10		109.72	114.80	Very poor recovery; only small to 10 cm pieces; qtz + aspy + py stringers		3		1	2		
				At 114.66 - 114.8m gouge zone sheared to moderately faulted at 60 deg; 1-3mm stringers throughout							
10		114.80	114.97	Sulphide - Quartz vein at 60 deg; bottom contact of gougy shear and highly alt'd zone at 60 deg; v f g to 3mm grains; shear/fault related?		2		2	1	1	
10		114.97	121.92	Moderately to weakly alt'd; At 115.5m slip face with minor gouge at 30 deg to CA		3		2	1		
				Sheared to gougy sections; moderately fractured with gouge in btw pieces of broken GND							
				At 117.3m = pyritic slip at 40 deg							
				At 117.6m = fracture foliation at 30 deg; 118.6m - 118.87m = broken core with cb on fracture surfaces; At 118.95m fracture foliation at 10 deg and 160 deg							
				At 119.5 - 119.7m, 4 X 0.2 - 0.3 cm py +/- aspy vnlts at 60							
				At 119.8 - 119.9m = minor gouge to shr at 20 deg to CA							
				At 120.45 - 121.4m = multiple <1cm qtz (sheeted?) vnlts at 30 to 25 deg							
				At 120.65m slip at 150 deg relative to vnlts; planar with sericite							
				At 121.18m - pyrite vnlt at 70 deg at 90 deg to quartz veinlets (py + aspy + aspy + qtz)							
				At 121.65 - 122m = broken core							
10		121.92	123.02	GND, moderately altered due to quartz veinlets' local pyritic fracture filling (1mm)		4		3	2		
				At 122.6m at 130 deg (relative to qtz vnlts) is qtz-carb vnlt (o.3mm) with tr py							
10		123.02	123.99	Shear GND; light green; sheared to gg (irregular); quartz-py _ aspy vns at upper and lower contacts; minor gouge at upper and lower contacts as well		4		3	2		
				At 123.99m pyritic slip at 43 deg to CA parallel to pyrite vein							
10		123.99	126.49	Slightly less alt'd than prev; multiple quartz (+/- cb) vnlts with aspy-py; at increasingly low angle to CA		3		3	2		
				At 124.57m sericitic slip face at 15 deg, parallel to veinlets							
				Core moderately broken; mnr veining; at 125.05m slip at 60 deg							
10		125.47	126.49	increased alteration of GND; common low angle slip/shr faces and some veining; At 125.47 - 125.49m = gougy shear at 45 deg to CA; At 125.98m slip at 10 deg to CA with stria at 60 deg		4		3	2		
10		126.49	128.40	Less alt'd GND; low angle veins moderate alteration; qtz +/- py and aspy		2		1	1		
10		128.40	129.35	Increasingly altered GND due to qtz vn, 1 cm with py on margins		4		3	2		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

PAGE 5 of 18

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA05048696 Return Samples
										Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
4	1	0.3	2.5	50	45	0.5	q/cb	2	0	5.0			0.3									B292801	104.37	105.60	0.357			VA05049598	1.23	
4	1	0.3	2.5	50	45	0.5	q/cb	2	0	5.0			0.3									B292802	104.37	105.60	0.407	DUP		VA05049598	1.23	
2	6	1.0	2.0	60		2.0	arg/cb	5	0	50.0			20.0									B292803	105.60	106.68	0.053			VA05049598	1.08	
3	4	0.5	3.0	30		1.0	cb/arg	4	0	0.5													(105.6 | 105.65)			pyrite +/- aspy ant qtz/cb vnlts			
2	3	0.3	1.0	60		1.0	cb/arg	3	0	0.5												B292804	106.68	107.20	0.061			VA05049598	0.52	0.3
3	3	0.3	2.0	60		1.0	cb/arg	3	0	2.0			0.2									B292805	107.20	108.20	0.101			VA05049598	1.00	0.417
2	3	0.2	0.5	60		2.0	qtz/ser/cb	3		0.2												B292806	108.20	109.72	0.311			VA05049598	1.52	0.916
4	1	0.3	4.0	50		0.5	q/cb	2		5.0			8.0									B292807	109.72	111.25	0.302			VA05049598	1.53	0.878
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292808	111.25	112.78	0.067			VA05049598	1.53	<0.005
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292809	111.25	112.78	0.076	PD/CA		VA05049598	1.53	
																						B292810	STANDARD 5E		1.520	5E		VA05049598		
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292811	112.78	114.30	0.056		Qtz +/- py vnlts	VA05049598	1.52	0.483
2	6	0.2	0.5	60		0.5	cb/arg	3		25.0			5.0									B292812	114.30	114.80	0.140		Vnlts in gouge	VA05049598	0.50	0.424
1	6	12.0	12.0	60		5.0	qtz/cb	4		50.0			10.0									B292813	114.80	114.97	1.785		High Sulphides	VA05049598	0.17	
1	1	5.0	5.0	60		5.0	qtz	2		10.0			3.0																	
2	2	0.6	1.5	45	60	3.0	cb/arg	3		0.8			0.1									B292814	114.97	115.82	0.118			VA05049598	0.85	
2	3	0.2	0.8	50			cb/arg	3		2.0			0.5									B292815	115.82	117.35	0.138			VA05049598	1.53	0.521
1	6	1.5	1.5	45		5.0	se/cb/arg	3		8.0			4.0		4.0								(116.65 | 116.67)			Py + sph + qtz/cb vn			
																						B292816	BLANK		<0.005			VA05049598		
4	1	0.5	2.0	60	50	0.5	qtz/ser	2		20.0			2.0									B292817	117.35	118.87	0.195			VA05049598	1.52	0.691
4	6	0.3	1.2	60		1.5	se/cb/qtz	3		60.0			5.0									B292818	118.87	120.40	0.171		py/aspy vnlts; mnr sulph in qtz vnlts	VA05049598	1.53	0.591
5	1	0.4	3.0	50	60	0.5	ser/qtz	1		3.0			0.8																	
10	1	0.8	5.0	30	25	5.0	se/qtz	2		3.0			0.8									B292819	120.40	121.92	0.189		multiple qtz +/- py vnlts	VA05049598	1.52	0.886
2	6	0.3	0.8	30		0.6	se/qtz/cb	2		50.0			4.0										(121.18				py/aspy +/- qtz vnlt			
2	6	0.3	0.4	70		1.5	se/arg/qtz	2		60.0			15.0																	
4	1	0.8	3.0	40	30	3.0	ser/arg/qtz	3		3.0			1.5									B292820	121.92	123.02	0.160			VA05049598	1.10	0.524
2	3	0.3	0.5	130		1.0	cb/qtz/ser	2		0.8																				
1	1	7.0	7.0	30		5.0	arg/cb/ser	4		18.0			6.0									B292821	123.02	123.99	0.466			VA05049598	0.97	0.516
1	1	7.0	7.0	30		5.0	arg/cb/ser	4		18.0			6.0									B292822	123.02	123.99	0.772	DUP		VA05049598	0.97	
																							(123.02 | 123.08)			qtz-py-aspy vn, upper contact	VA05049598		
1	3	2.5	2.5	43		3.0	arg/cb/ser	3		22.0			4.0										(123.96 | 123.99)						
5	1	0.6	4.0	20	30	0.5	ser/cb/arg	3		2.0			3.0									B292823	123.99	124.97	0.340			VA05049598	0.98	
3	1	0.4	2.0	50		1.0	ser/cb/arg	3		0.8			0.4									B292824	124.97	125.47	0.266			VA05049598	0.50	0.707
3	1	0.5	2.0	20	30	1.5	ser/cb/arg	3		5.0			3.0									B292825	125.47	126.49	0.470		Qtz vnlts +/- py, aspy vnlts, low angle	VA05049598	1.02	
2	1	0.7	1.5	20		2.0	ser/cb/arg	2		4.0			1.5									B292826	126.49	128.07	0.155			VA05049598	1.58	0.703
1	1	0.3	0.3	20		1.0	ser/cb/arg	2		4.0			1.5									B292827	128.07	128.40	0.179			VA05049598	0.33	0.709
1	1	1.0	1.0	25		10.0	ser/cb/arg	4		4.0			2.0									B292828	128.40	129.35	0.066			VA05049598	0.95	
1	1	1.0	1.0	25		10.0	ser/cb/arg	4		4.0			2.0									B292829	128.40	129.35	0.060	PD/CA		VA05049598	0.95	
																						B292830	STANDARD 6F		2.830	6F		VA05049598		

DRILL HOLE # : DG05-282C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		129.35	131.70	Slightly less altered GND than prev; At 129.85m = low angle quartz vns (20 deg)		4		2	2	
				At 131.1m quartz-cb vnlts at 35 deg; At 131.2m low angle qtz/cb fracture filling with ser slip faces at 15 deg; At 131.25m at 140 deg, quartz open space filling; euhedral quartz xtls in 1 cm vug						
10		131.70	132.05	Mnr faulting with associated veining		4		3	3	
				At 131.7 - 131.76m = Quartz vein with high sulphides (py gen; at lower margin)						
10		132.05	133.10	Less alt'd than prev; less shr; carb-qtz vn with trace sulphides at low angle (15 deg) to CA		3		2	2	
10		133.10	144.45	Less alt'd than prev; still dk bt, occasional alt'n adj to vein sets; relatively less fractured and sheared than prev		1		1	1	
				At 135.1 - 135.14m = FLT GG at 40 deg to CA; ser-arg-carb alt'd; no vis min; At 135.63m = graphitic slip with striae at 30 deg; face at 15 deg						
				Sheeted veins of qtz +/- coarse grained aspy/py; spacing btw 5 and 20cm; <1cm diam; At 136.58m graphitic slip face at 25 deg with straie at 20 deg; tr py; At 136.6 - 136.75m 0.2 mm fracture filling by carb-arg (clay) at 150 deg relative to the previous slip face						
				Generally uniform; weakly alt'd GND with mnr alteration associated with thin qtz vns (+/- tr py-aspy); at 138.38m slip shr face @ 25 deg; mnr carb coatings						
				Sim to abv						
				Mnr veining wi a "xenolith" of dk mafic (perhaps pot alt'd?) (78% bt + qtz + feld)						
				Similar to abv; slightly more vnlts; (qtz +/- py/aspy) gen at 30 deg to CA						
				Similar to abv; slightly more aspy in strings and local disseminations; irregularly fractured and slightly more alt'd from 143.76m						
				At 144.45 - 144.66m, moderate ser-cb-arg alt'n assoc'd with qtz-aspy-py vn at 40 deg to CA		3		2	2	
10		144.66	147.35	144.66 - 147.35 Weakly to locally alt'd GND; 145.4 - 145.75m = multiple qtz +/- py vnlts, vein to blotchy aspy selvages (0.7%)		1		1	1	
10		147.35	148.42	Increased alteration due to mnr shearing; mnr - tr qtz +/- py veining		3		3	3	
10		148.42	150.55	Locally wkly alt'd GND; generally unalt'd; mnr qtz +/- py/aspy vnlts		1		1	1	
10		150.55	153.00	Generally wkly to mod'ly ser-cb-arg alt'd; local mnr zones of relatively unalt'd GND		2		2	2	
				151.3 - 151.32 = Shr to gouge; high argillic alteration at 20 deg to CA					4	
				151.6 Slip/Shr plane at 30 deg to CA; slightly pyritic and gougy						
10		153.00	153.92	Moderately alt'd GND due to qtz - py/aspy vn (grey qtz); At 153.63 - 153.68m; 153.72 - Shr/slip at 30 deg parallel to vn		3		4	2	
				Locally blotch aspy/py in selvages (<2%)						
10		153.92	156.40	Weakly to locally relatively unaltered (grey) GND		2		2	1	
				At 154.15m - black (pyritic) slip at 40 deg						
10		156.40	156.97	Sericite altered GND; increasingly altered towards base of interval		3		2	1	
				At 156.76 - 156.78m = Qtz cb vn wi 1-3% py/aspy						
10		156.97	157.50	Weakly alt'd GND		2		1	1	
				At 157.5m = slip (pyritic face) at 40 deg						
10		157.50	159.40	Moderately to strongly alt'd GND; wkly sheared; shr fracts commonly filled with cb/qtz; some qtz +/- py veining; core soft		3		4	2	

DRILL LOG LEGEND P2

Date: June 14-17, 2005

PAGE 10 of 18

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval							
						Selvages				Sulphides										Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	ascordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048696 Return Samples
4	1	0.8	4.0	10	20	10.0	se/c	3		0.5			0.5									B292831	129.35	131.06	**0.198**			VA05049598	1.71	0.683
2	3	0.5	1.5	10	35	1.5	cb	3		0.4			0.2																	0.684
1	3	0.5	1.5	10	35	105.0	ser/cb	3		0.4			0.2									B292832	131.06	131.70	**0.233**			VA05049598	0.64	0.57
1	1	1.0	1.0	15		2.0	se/arg/cb	3		0.5			0.3									B292833	131.70	132.05	**0.729**			VA05049598	0.35	
1	1	6.0	6.0	20		1.0	ser/cb/arg	2		20.0			2.0										(131.7	131.76)			Qtz and py at upper contact, flt'd?			
2	1	0.8	2.0	15	20	1.0	se/cb/arg	2		0.5			0.4									B292834	132.05	133.10	**0.122**			VA05049598	1.05	0.963
2	4	1.0	1.0	15		2.0	cb/ser/arg	3		0.8			0.6										(132.4	132.41)			Cb-qtz vn)			
3	1	0.6	2.0	15		0.8	se/cb/arg	2		0.8			0.4									B292835	133.10	134.11	**0.086**			VA05049598	1.01	
1	1	1.0	1.0	140		0.5	se	1		0.5			0.4										(134.45	134.46)			Qtz vein			
																						B292836	BLANK		**<0.005**			VA05049598		
1	1	1.0	1.0	30		5.0	se/cb/arg	2		0.5			0.4									B292837	134.11	135.64	**0.091**			VA05049598	1.53	0.74
1	1	1.0	1.0	30		5.0	se/cb/arg	2		0.5			0.4										(134.55	134.56)			Qtz vn			
5	1	0.5	5.0	20	25	0.5	se/cb/arg	2		1.5			1.5									B292838	135.64	137.16	**0.107**			VA05049598	1.52	0.983
v	1	0.3	1.2	35	30	0.5	se/cb/arg	2		0.4			0.4									B292839	137.16	138.68	**0.076**			VA05049598	1.52	0.855
6	1	0.3	2.0	40	35	0.5	se/cb/arg	2		1.0			0.5									B292840	138.68	140.21	**0.186**			VA05049598	1.53	0.446
2	1	0.3	0.5	40		0.5	se/qtz/cb	2		1.0			0.5									B292841	140.21	141.73	**0.198**			VA05049598	1.52	0.366
2	1	0.3	0.5	40		0.5	se/qtz/cb	2		1.0			0.5									B292842	140.21	141.73	**0.190**	DUP		VA05049598	1.52	
6	1	0.3	2.0	30		0.5	ser/qtz	2		1.0			1.0									B292843	141.73	143.26	**0.165**		Qtz py/aspy stringers	VA05049598	1.53	0.361
																						B292844	143.26	144.45	**0.410**		Qtz py/aspy stringers	VA05049598	1.19	
1	1	1.0	1.0	40		10.0	se/cb/arg	2		3.0			5.0									B292845	144.45	144.66	**0.807**			VA05049598	0.21	
																							(144.55	144.56)			Qtz aspy vn			
8	1	0.6	4.0	42	30	0.5	qtz/ser/cb	1		0.5			0.7									B292846	144.66	146.10	**0.186**		Small qtz py/aspy vnlts	VA05049598	1.44	0.282
5	1	0.6	3.0	25		0.5	qtz/ser/cb	1		0.5			0.5									B292847	146.10	147.35	**0.116**		Small qtz py/aspy vnlts	VA05049598	1.25	0.298
2	3	0.5	1.0	30		10.0	se/cb/arg	1		0.5			0.5									B292848	147.35	148.42	**0.052**			VA05049598	1.07	0.281
2	3	0.5	1.0	30		10.0	se/cb/arg	1		0.5			0.5									B292849	147.35	148.42	**0.052**	PD/CA		VA05049598	1.07	
																						B292850	STANDARD 3C		**0.094**	3C		VA05049598		
4	1	0.4	2.0	30		1.0	se/qtz	2		0.5			0.4									B292851	148.42	149.35	**0.042**		mnr qtz +/- py, aspy vnlts	VA05049598	0.93	
3	1	0.4	2.0	30		1.0	ser/qtz	2		0.5			0.4									B292852	149.35	150.55	**0.038**			VA05049598	1.20	0.215
3	1	0.2	1.0	30		1.0	se/qtz	3		0.5			0.4									B292853	150.55	150.88	**0.064**			VA05049598	0.33	
2	6	0.3	0.5	30		2.0	se/cb/qtz	2		10.0			5.0									B292854	150.88	152.40	**0.038**			VA05049598	1.52	0.157
2	1	0.2	1.0	30		1.0	ser	1		0.5			0.4										(151.6	151.65)			py/aspy strgrs			
2	1	0.2	1.0	30		1.0	qtz/ser	1		0.5			0.4									B292855	152.40	153.00	**0.080**			VA05049598	0.60	0.219
																						B292856	BLANK		**<0.005**			VA05049598		
5	1	0.3	3.0	40	30	2.0	ser/arg/cb	4		5.0			3.0									B292857	153.00	153.92	**0.333**			VA05049598	0.92	
1	1	5.0	5.0	30		10.0	ser/arg/cb	4		5.0			4.0										(153.63	153.68)			Qtz aspy/py vein at 30 deg			
3	6	0.1	0.2	30		0.5	se/cb/arg	2		20.0			2.0									B292858	153.92	155.45	**0.077**			VA05049598	1.53	0.33
1	1	0.8	2.0	40		3.0	se/arg/cb	2		2.0			1.0									B292859	155.45	156.40	**0.017**			VA05049598	0.95	0.302
																							(156.39	156.4)			Qtz +/- py/aspy vn			
2	1	0.2	0.5	25		2.0	se/cb	3		0.4			0.3									B292860	156.40	156.97	**0.027**			VA05049598	0.57	
1	3	1.5	1.5	25		3.0	se/cb	3		1.5			0.7										(156.76	156.78)						
2	1	0.1	0.3	25		0.5	se/cb	2		0.5			0.5									B292861	156.97	157.50	**0.019**			VA05049598	0.53	0.469
2	1	0.1	0.3	25		0.5	se/cb	2		0.5			0.5									B292862	156.97	157.50	**0.022**	DUP		VA05049598	0.53	
3	1	0.5	1.5	25		2.0	se/arg/cb	4		0.5			0.4									B292863	157.50	158.50	**0.047**		Mnr qtz +/- py vnlts	VA05049598	1.00	
10	4	0.2	5.0	1		0.5	cb	2																						
2	1	0.5	1.5	25		2.0	se/arg/cb	2		0.5			0.5									B292864	158.50	159.40	**0.033**		Mnr qtz +/- py vnlts	VA05049598	0.90	0.243

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMQN = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		159.40	161.90	Higher Cb alt'n; core more competent (hard); increased veining		2		2	4	
				Increased silica; local pyrite stringers/fracture filling						
				161.35 - 161.41m = 2 X 0.5 cm zones of high pyrite mineralization in highly altered GND; irreg, though generally at 30-40 deg						
10		161.90	164.45	Non to locally weakly unaltered GND		1		1	1	
				From 162.75 to 162.76m: Qtz vein (gy clr qtz) with 2% aspy ± py. Noted alt'n is local.		2		3	1	
10		164.45	170.80	Highly argillic altered GND; common unaltered biotite; generally soft; rare veining; not a fault		3		5	2	
				gouge; rare veins						
				Core slightly more competent; less alt'd than previous and slightly less veining						
10		170.80	171.22	Sericite +/- argillic altered GND adjacent to 2-3cm qtz vn (with up to 3-4% aspy); no mineralization visible in the selvage		2		1		
10		171.22	173.12	Weakly to locally strongly alt'd GND		2		3	2	
				GND more competent adj to qtz vnlts, becoming more argillic alt'd within 10cm of vein; commonly cb +/- qtz on fracture surfaces; sampled relative to larger veins/veinlets		3		4	3	
				At 172.38m aspy-py coated (slip?) surface at 35 deg						
				Qtz vein at 35 deg (172.84 - 172.87m) with dk py; blebs of aspy and py-aspy coated lower contact; dominantly arg-ser-cb alt'n on either side						
10		173.12	175.00	Sericite alteration dominant with locally increased argillic alteration;		3		3	2	
				Nice py-aspy bearing vn (with shear?) at 173.2 - 173.25; slip/shr surfaces at 50 deg; py-aspy coated; dominantly se alt'n						
				Qtz-aspy-py vein; grey to white qtz, sulphides dominantly on margins with 2-3 mm and of spy through middle; black py (possibly due to shr) on margins						
10		175.00	175.86	Weakly ser-chl-arg alt'd GND with multiple thin qtz vnlts; increasing argillic alt'n towards the base		1	2	1	1	
10		175.86	177.40	High argillic alteration; moderately - highly gougy, some quartz veining		3	1	4	2	
10		177.40	177.53	White to grey qtz vn, 3% aspy wi 1-2% py at margins						
10		177.53	178.65	Argillic + sericitic alt'd GND (Lt gn to white)		3		3	2	
10		178.65	179.44	Relatively unaltered GND		1		1		
10		179.44	180.60	Intensely arg/ser alt'd GND due to white quartz veining, poor mineralization		4		5	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL															Interval						
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048596 Return Samples
6	4	0.2	3.0	25		0.5	cb/ser	2		1.0												B292865	159.40	160.38	0.033			VA05049598	0.98	
3	6	0.2	1.0	25		1.0	cb.ser.qtza	3		80.0			2.0																	
3	6	0.2	1.0	25	30	0.5	cb/qtz	3		80.0			2.0									B292866	160.38	161.90	0.106			VA05049598	1.52	0.285
2	6	0.5	1.5	30		0.5	cb/qtz	3		80.0			2.0																	
4	4	0.3	1.5	120		0.5	qtz.cb	3		0.5			0.2																	
3	1	1.0	2.5	60		0.5	se/qtz	2		0.7			0.5									B292867	161.90	163.07	0.110			VA05049598	1.17	0.274
3	1	1.0	1.0	60		0.2	qtz/cb	2		0.3			0.5										(162.75	162.76)						
3	1	1.0	0.3	60		0.5	se/cb	2		0.5			0.5									B292868	163.07	164.45	0.091			VA05049598	1.38	0.308
3	1	1.0	0.3	60		0.5	se/cb	2		0.5			0.5									B292869	163.07	164.45	0.096	PD/CA		VA05049598	1.38	
																						B292870	STANDARD 2B		3.200	2B		VA05049598		
3	3	0.1	0.5	45		0.5	arg/cb/se	4		0.5			0.2									B292871	164.45	165.23	0.072		trace veining	VA05049598	0.78	0.303
2	1	0.2	1.0			0.5	arg/cb/se	4		1.0			1.0									B292872	165.23	166.12	0.086			VA05049598	0.89	
1	1	0.5	0.5			0.5	cb/arg/ser	4		2.0			3.0										(165.8	165.81)						
3	1	0.8	4.0	40		0.5	cb/ser/arg	4		1.5			0.8									B292873	166.12	167.64	0.094			VA05049598	1.52	0.266
3	1	0.6	3.0	40		1.0	cb/ser/arg	4		1.0			0.5									B292874	167.64	169.16	0.068			VA05049598	1.52	
2	1	0.7	4.0	40	45	0.5	ser/cb/qtz/arg	2		1.0			0.6									B292875	169.16	170.41	0.100			VA05049598	1.25	
																						B292876	BLANK		<0.005			VA05049598		
																						B292877	170.41	170.80	0.169			VA05049598	0.39	
2	1	3.0	4.0	45		11.0	se/cb/arg	4		1.0			4.0									B292878	170.80	171.22	0.407			VA05049598	0.42	
2	1	3.0	3.0	45		10.0	ser	4		1.5			4.0										(170.9	170.93)			Good qtz-aspy vein			
3	1	1.3	4.0	55		5.0	arg/ser/cb	4		1.5			1.5									B292879	171.22	172.21	0.035		Qtz py/aspy vnlts	VA05049598	0.99	
3	1	1.0	4.0	45		2.0	se/arg/cb	3		1.5			1.5									B292880	172.21	172.84	0.367			VA05049598	0.63	
2	1	3.0	4.0	35		10.0	ser/arg/cb	4		2.0			1.5									B292881	172.84	173.12	0.213			VA05049598	0.28	
1	1	3.0	3.0	35		10.0	se/arg/cb	4		3.0			1.5										(172.84	172.87)						
																						B292882	172.84	173.12	0.166	DUP		VA05049598	0.28	
3	1	5.0	5.5	50		11.0	se/cb/arg	3		7.0			2.0									B292883	173.12	173.50	22.800			VA05049598	0.38	
1	1	5.0	5.0	50		10.0	se/cb/arg	3		7.0			2.0										(173.2	173.25)						
2	1	4.0	5.0	60		10.0	arg/se/cb	4		4.0			5.0									B292884	173.50	173.87	0.376			VA05049598	0.37	
1	1	4.0	4.0	60		10.0	se/cb/arg	4		4.0			5.0										(173.74	173.78)						
2	1	0.2	0.8	45		0.5	se/cb/arg	2		0.3			0.2									B292885	173.87	175.00	0.123			VA05049598	1.13	
4	1	0.4	1.5	5	5	0.5	ser/qtz/chl	2		0.4			0.3									B292886	175.00	175.86	0.072			VA05049598	0.86	
5	1	0.6	4.0	45		10.0	arg/ser/chl	4		0.9			0.6									B292887	175.86	177.40	0.156		Qtz vnlts with py/aspy	VA05049598	1.54	
1	1	13.0	13.0	50		10.5	arg/se/cb	3		1.5			3.0									B292888	177.40	177.53	0.056		Qtz vn with 1.5 % py + 3% aspy	VA05049598	0.13	
1	1	13.0	13.0	50		10.5	arg/se/cb	3		1.5			3.0									B292889	177.40	177.53	0.052	PD/CA	Qtz vn with 1.5 % py + 3% aspy	VA05049598	0.13	
																						B292890	STANDARD 7G		4.510	7G		VA05049598		
2	1	0.5	1.0	50		10.5	arg/ser/chl	3		0.5			0.4									B292891	177.53	178.65	0.090			VA05049598	1.12	
1	6	0.4	0.4	50		1.0	arg/ser	4		70.0			3.0																	
3	1	0.2	1.0	40	30	0.5	ser/arg	1		1.0			0.4									B292892	178.65	179.44	0.093			VA05049598	0.79	
3	1	6.0	10.0	40		11.0	arg/ser	4		2.0			0.5									B292893	179.44	180.60	0.143			VA05049598	1.16	
1	6	0.3	0.3	130		1.0	arg/ser/cb	3		60.0			3.0																	
1	1	3.0	3.0	40		10.5	arg/ser/cb	4		2.0			0.5										(180.42	180.48)			Qtz vn wi mnr py/aspy			

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.60	185.06	Weakly to locally moderately alt'd GND; alt'd adj to veins/veinlets		1		1	1	
				selvages' alt'n:		2		3	2	
				At 182.56 - 182.80m = Qtz aspy vein set at 30 deg to CA; 60% aspy in vnlt; wi qtz						
				Qtz vein with coarse grained py/aspy up to 12% overall; sulphides commonly on margins, sample includes 10cm of alt'd GND (ser+cb+arg alt'n)						
10		185.06	186.37	Weak sericite-argillic alteration of GND; 1-2 qtz-aspy +/- py vnlts		1		1	1	
10		186.37	187.04	Similar GND to prev; wi multiple 1-6 cm "dark" " xeno's(?)"" may be potassic alt'd GND (bt +/- hb +/- feld = dominant mins; weak silicic (silicification) rim around "xenos"; no increased mineralization assoc'd		1	1	1	1	3
10		187.04	189.37	Weak sericite +/- arg alt'd GND		1		1	1	
				Sheeted vnlts of qtz and aspy-qtz; gen 0.5 cm; gen at 30-40 deg to CA; up to 80% aspy (best btw 187.65 - 188.6m)		2		2	1	
				Sim to abv; less intense veining; with less sulphides and frequency of vnlts						
10		189.37	190.00	Sim to 186.37-187.04 interval; Potential potassic alt'd GND "xenos" = 15% of core; some aspy rimming on xeno as well as a 0.7mm veinlet of 80% aspy		1	1	1	1	3
				At 189.76m slip at 60 deg to CA; At 189.8m - 189.89m aspy vn (90% aspy); med grained; increased cb alt'n						
10		190.00	190.90	High argillic alt'd GND; wi cb alt'n; aspy qtz-cb vn near base; 1 cm thick		2		4	2	
				Increased carbonate alt'n and veining						
10		190.90	191.80	GND wi multiple dark/more mafic "xenos" (again, perhaps potassic alt'd?); weakly chl alt'd xenos - BQAH? (60); relatively poor min'n		1	1	1	1	
80	191.8-218.67	191.80	192.90	Metasediments (hornfels?) - alternating btw BQAH (60) and QZZ (70); alternating btw dk brn (wi red tint) to light gy (QZZ); rare GND (191.53 - 191.58m); Common barren white quartz veins; contact @ 60 deg; At 191.58m-191.62m = Irreg qtz vn; At 191.73m - 191.78m = Qtz vn at 80 deg; At 191.79 - 191.85m = Qtz vn at 80 deg						1
80		192.90	195.17	Silicified (bleached) metased with QZZ and Qtz veins; Qtz veins/vnlts generally barren or wi tr py		2				2
				selvage alt'n:				2		
80		195.17	196.35	Weakly alt'd though metam. Seds; 0.6mm leucocratic bands (qtz) wi thin bt lam; mnr qtz veining at 30 deg; GND "bleb" at base (196.3 - 196.35m)		1				1
80		196.35	198.12	Bleached metaseds; generally lt brown to off wht to grey (lt); multiple qtz vnlts to vns; mnr sulphides where cb present		4			1	3
				At 196.6m shear plane at 25%						
				197.5 - 197.58m Qtz vns - wht						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS | **% of VEIN & DISSEMINATED MATERIAL**

#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Selvages Alteration	Selvages (0-5)	Ox. State 0-5	Sulphides pyrite	Sulphides pyrrhotite	Sulphides chalcopyrite	Sulphides arsenopyrite	Sulphides bismuthite	Sulphides sphalerite	Sulphides visible gold	Sulphides other	Oxidation oxide	Oxidation scordite	Oxidation biotite	Oxidation other	Sample Number	Interval From	Interval To	Au (g/T)		Notes	CSV	Width (m)	VA05048596 Return Samples
4	1	0.6	4.0	30	40	1.0	ser/cb/arg	2		0.5			0.6									B292894	180.60	181.36	**0.141**			VA05049598	0.76	
3	1	0.6	2.0	30		0.5	ser/cb/arg	2		0.5			0.6									B292895	181.36	182.46	**0.080**			VA05049598	1.10	
																						B292896	BLANK		**<0.005**			VA05049598		
4	1	0.7	4.0	30		1.0	se/cb/arg	3		5.0			60.0									B292897	182.46	182.88	**0.276**		4 Quartz aspy vnlts; aspy up to 60%	VA05049598	0.42	
4	1	0.4	2.5	30	40	2.0	se/cb/arg	2		0.7			0.4									B292898	182.88	183.93	**0.076**			VA05049598	1.05	
5	1	1.5	4.0	30		10.0	ser/cb/arg	2		2.0			15.0									B292899	183.93	184.88	**0.187**			VA05049598	0.95	
1	1	1.5	1.5	30		10.0	ser/cb/arg	2		2.0			15.0										(184.14	184.16)			Qtz aspy vn = 15% aspy			
1	1	8.0	8.0	25	30	10.0	ser/cb/arg	3		4.0			12.0									B292900	184.88	185.06	**0.922**		Qtz py/aspy vn; c g py and aspy	VA05049598	0.18	
2	1	1.0	1.5	30		2.0	arg/se	2		1.0			0.5									B292901	185.06	186.37	**0.563**		Qtz-Aspy vnlt	VA05049598	1.31	
2	1	1.0	1.5	30		2.0	arg/se	2		1.0			0.5									B292902	185.06	186.37	**0.724**	DUP	Qtz-Aspy vnlt	VA05049598	1.31	
1	1	0.5	0.5	50		1.0	cb/arg/ser	3		3.0			11.0									B292903	186.37	187.04	**0.182**			VA05049598	0.67	
3	1	0.5	2.0	30		0.5	qtz/ser	2		2.0			1.0									B292904	187.04	187.45	**0.165**			VA05049598	0.41	
6	6	0.7	5.0	30	40	0.5	qtz/ser	2		4.0			80.0				0.5					B292905	187.45	188.98	**0.643**	*	Good sheeted qtz & aspy qtz vnlts	VA05049598	1.53	
3	1	1.0	4.0	30	40	1.0	qtz/ser	2		2.0			4.0									B292906	188.98	189.37	**0.298**			VA05049598	0.39	
2	6	0.9	1.5	60	40	1.0	qtz/cb/ser	2		4.0			80.0									B292907	189.37	190.00	**3.220**		0.9cm aspy vn	VA05049598	0.63	
2	6	0.8	1.5			10.0	cb/ser/arg	2		4.0			80.0									B292908	190.00	190.90	**0.334**		aspy vn (0.8cm)	VA05049598	0.90	
4	4	1.0	4.0			20.0	cb	4		0.8			0.5																	
4	4	1.0	4.0			20.0	cb	4		0.8			0.5									B292909	190.00	190.90	**0.333**	PD/CA		VA05049598	0.90	
																						B292910	STANDARD 5E		**1.450**	5E		VA05049598		
2	4	0.5	1.0	30	20	0.3	cb/se	1														B292911	190.90	191.80	**0.140**			VA05049598	0.90	
5	1	2.2	10.0	40																		B292912	191.80	192.90	**0.139**			VA05049598	1.10	
4	1	2.0	8.0	30																		B292913	192.90	193.80	**0.179**		Small Qtz-aspy-py veinlet	VA05049598	0.90	
1	1	0.3	0.3	35		1.0	qtz/ser/cb	2		3.0			20.0																	
7	1	2.0	12.0	30	25	2.0	qtz/ser/cb	2		0.4			0.2									B292914	193.80	195.17	**0.082**			VA05049598	1.37	
7	1	1.5	10.0	30	25	2.0	qtz/ser=	2		0.7			0.4									B292915	195.17	196.35	**0.016**			VA05049598	1.18	
																						B292916	BLANK		**<0.005**			VA05049598		
7	1	1.0	10.0	30	70	11.0	se/qtz	3		0.6			0.6									B292917	196.35	197.15	**0.014**			VA05049598	0.80	0.641
7	1	1.0	10.0	70	30	11.0	ser/qtz	3		0.5			0.5									B292918	197.15	198.12	**<0.005**			VA05049598	0.97	
1	1	8.0	8.0	70		11.0	ser/qtz	3		0.5			0.5										(197.5	197.58)						
3	4	0.4	2.0	40		0.5	cb/ser	1																						

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		198.12	202.76	Weakly alt'd metaseds; dk brn/grey; locly lt gy adj to some qtz vns; At 198.5m MSED foliation at 70 to 50 deg;		1				2
				Subtle fracture foliation at 140 deg relative to MSEDs and QV's						
				At 202.69m MSED foliation at 60 deg						
80		202.76	213.12	Weakly alt'd MSED (wi weak potassic alt'n?); local qtz-py +/- aspy veinlets; 202.76 - 203.2m fractured core; At 202.98 - 203.05m GND ser+arg+cb alt'd (2,2,3); parallel to MSED banding; At 204.7m MSED foliation at 70 deg to CA		2				1
				Vnlts at 160 - 140 deg relative to MSED; may be shr/fract derived						
				At 208.85 - MSED foliation at 70 deg; At 210.05m Qtz-Py vn at 150 deg relative to MSED						
				At 210.35 - 210.43m - Qtz vn (sample includes alt'd MSED wi 2-3% diss py/aspy)						
				At 210 m MSED at 65 deg with Qtz vning at 150 deg						
				At 210.97 - 211.02m = Shr/micro flt at 60 deg; ox'd and slightly gougy core; 211.36 - 211.46 QV at 80 deg						
80		213.12	213.86	MSED cont'd; relatively unalt'd; dk-med brown grey; few vns; At 213.50 fol'n at 80 deg		1				
80		213.86	218.67	MSED - mod'ly alt'd to med lt brn-grey due to qtz vns; locly wkly shr'd at 30 deg		3			1	
				At 215.18 m MSED fol'n at 55-60 deg; local K (bt) alt'n envelopes around qtz vnlts						
				Local relatively unalt'd zones bwtn 215.52-216.10m:		1			1	
				A few qtz/cb veins wi py/aspy; no min'n vis in selvage; x-cutting MSED fol'n; mnr shearing here; blebs of sph locally in qtz/cb vns						
				Moderate se-alt'n; large barren wht to slightly translucent QV's @ 217.10-217.43m; parallel to MSED fol'n at 50-60 deg						
10		218.67	221.62	Less alt'd GND; dk brn-gy; wk ser alt'n overall		1			1	
				At 221.45m MSED fol'n at 50 deg wi qtz vns/vnlts at 160-140 deg - barren		3			1	
80		221.62	228.86	Ser alt'd MSED; lt-med grn-gy, locally slightly sheared; Qtz vning wi tr-1% py; locally mod'ly silicified; MSED fol'n btw 50-70 deg wi both parallel and x-cutting Qtz vns; parallel vns generally thicker; local qtz-cb vns		1				
				Cross cutting vns locally with 1-3% py and sph						
				At 224.32m MSED slightly sheared to 40 deg wi cross-cutting fract fol'n at 120 deg; common parallel qtz vns wi locly tr-1% py						
				At 225.85m MSED foliation at 60 deg						
				At 227.24m MSED foliation at 57 deg						
80		228.86	230.73	Less alt'd (?) MSED; At 229.15m MSED at 60 deg wi local qtz vnlts at 150 deg (229.25m); At 230.70m MSED at 55 deg						
80		230.73	234.60	MSED; generally wkly to mod'ly alt'd and light grn-gy; locally low ser alt'n' wi dk brn-gy bt; loc qtz-cb fract filling (wk shr) x-cutting MSED fol'n at 155 deg; poorly min'd wi loc wht qtz		3			2	

DRILL LOG LEGEND P2

Date: June 14-17, 2006

PAGE 10 of 18

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA06048696 Return Samples
						Selvages																								
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
10	1	0.5	4.0	60		0.0																B292919	198.12	199.64	0.012			VA05049598	1.52	0.523
1	1	2.0	10.0	60	0																	B292920	199.64	201.17	0.048			VA05049598	1.53	0.684
																							(200.5	200.52)						
10	1	1.5	15.0	70	140	0.5	ser/qtz	1		0.3												B292921	201.17	202.76	0.019			VA05049598	1.59	0.468
																						B292922	201.17	202.76	0.010	DUP		VA05049598	1.59	
8	1	0.3	5.0	70	140	0.5	ser/qtz	1		1.5			1.0									B292923	202.76	203.20	0.011			VA05049598	0.44	0.36
11	1	0.8	10.0	160	70	0.4	ser/qtz	1		0.3												B292924	203.20	204.78	0.01			VA05052041	1.58	
3	6	0.5	2.0	160		0.2	qtz/ser	1		60.0			4.0									B292925	204.78	205.74	1.655			VA05052041	0.96	0.275
8	1	0.5	3.0	160	70	0.2	qtz/ser	1		0.5			0.4																	
3	1	0.5	2.0	160	140	0.5	qtz/ser	1		25.0			3.0				0.5					B292926	205.74	206.60	0.109			VA05052041	0.86	0.476
11	1	0.3	4.0	160		0.2	qtz/ser	1		0.3			0.3																	
8	1	0.3	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292927	206.60	207.26	0.011			VA05052041	0.66	
6	1	0.4	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292928	207.26	208.79	0.013			VA05052041	1.53	
6	1	0.4	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292929	207.26	208.79	0.017	PD/CA		VA05052041	1.53	
																						B292930	STANDARD 1A		0.879	1A		VA05052041		
4	1	0.2	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292931	208.79	210.25	0.014			VA05052041	1.46	
1	1	8.0	0.8	140		1.0	q/ser	2		4.0			2.0									B292932	210.25	210.46	0.846		Qtz - py + aspy vn;	VA05052041	0.21	
4	1	0.3	2.0	140	70	0.5	qtz/ser	2		0.6			0.4									B292933	210.46	211.84	0.015			VA05052041	1.38	
10	1	10.0	16.0	140		0.4	ser/qtz	1		0.6			0.4									B292934	211.84	213.12	0.009			VA05052041	1.28	
1	1	10.0	10.0	80		1.0	ser/qtz	2															(212.36	212.46)						
2	6	0.2	0.3	35		1.0	ser/qtz	2		60.0			0.8									B292935	213.12	213.86	<0.005			VA05052041	0.74	
																						B292936	BLANK		<0.005			VA05052041		
6	1	1.2	4.0	150		10.0	qtz/ser	2		2.0			0.7									B292937	213.86	214.88	0.009			VA05052041	1.02	
3	1	2.2	4.0	50		0.3	qtz/ser	1		0.3			0.3									B292938	214.88	216.41	0.009			VA05052041	1.53	
4	1	0.2	1.0	150		0.6	k,ser	3		0.8			0.2																	
2	3	0.5	1.0	20	70	0.3	qtz/cb	1		0.3			0.3																	
3	3	1.0	4.0	165		1.0	cb/qtz	2		5.0			1.5									B292939	216.41	216.88	0.023			VA05052041	0.47	
2	1	1.0	2.0	70		0.2	qtz	2		0.3			0.3																	
3	1	16.0	20.0	50	60	11.0	se/qtz	3		0.2												B292940	216.88	217.93	0.008			VA05052041	1.05	
7	1	1.0	5.0	45		11.0	se/qtz	3		0.2												B292941	217.93	218.67	<0.005			VA05052041	0.74	
7	1	1.0	5.0	45		11.0	se/qtz	3		0.2												B292942	217.93	218.67	<0.005	DUP		VA05052041	0.74	
4	1	1.0	3.5	160		1.0	ser/qtz/cb	3		0.2												B292943	218.67	220.10	0.017			VA05052041	1.43	
3	1	0.8	2.5	140		0.8	k	3		0.2																				
4	1	0.8	3.0	140		2.0	ser/qtz/cb	3		0.2												B292944	220.10	221.62	0.016			VA05052041	1.52	
8	1	0.8	7.0	160		2.0	ser/qtz/cb	3		0.8			0.8									B292945	221.62	222.50	0.042			VA05052041	0.88	
4	1	0.6	3.0	160		0.5	ser/qtz	3		1.0			0.6									B292946	222.50	224.03	0.019			VA05052041	1.53	
2	4	0.5	1.0	160		1.0	ser/chl	3		0.5																				
2	1	0.8	2.0	160		1.0	ser/qtz	3		1.0			0.5		1.0															
6	1	0.5	3.0	40	50	1.0	ser/qtz	3		0.8												B292947	224.03	225.55	0.026			VA05052041	1.52	
5	1	0.4	3.0	60		1.0	ser	2		0.5												B292948	225.55	227.08	0.007			VA05052041	1.53	
10	1	0.3	5.0	140		0.3	ser	2		0.6																				
10	1	0.3	5.0	140		0.3	ser	2		0.6												B292949	225.55	227.08	0.008	PD/CA		VA05052041	1.53	
																						B292950	STANDARD 3C		0.091	3C		VA05052041		
5	1	0.5	4.0	60	162	0.3	ser/qtz	3		0.4												B292951	227.08	228.60	0.016			VA05052041	1.52	
2	1	0.3	0.6	130		0.1	ser/qtz	1		0.4												B292952	228.60	228.86	0.005			VA05052041	0.26	
3	1	0.5	2.0	150		0.5	ser/qtz	2		0.4												B292953	228.86	230.12	0.005			VA05052041	1.26	
3	1	0.4	2.0	140		1.0	ser	1	1													B292954	230.12	230.73	<0.005			VA05052041	0.61	
4	1	0.5	4.0	130		2.0	ser/cb	3		0.5												B292955	230.73	231.88	<0.005			VA05052041	1.15	
																						B292956	BLANK		<0.005			VA05052041		
4	1	2.0	4.0	130		3.0	ser	3		0.5												B292957	231.88	233.17	<0.005			VA05052041	1.29	

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MQD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		234.60	237.80	Increasing alt'n and shr (?); Rock softer; irregular to shr are dk py vns; increase wht qtz vns; lost competency; nearing a lower contact with GND dike; 235.4 - 235.41m Flt-shr gg at 165 deg to CA		3		2	2	
				At 237.44 - 237.47m Py-qtz vn wi 70% py, broken core; possibly highly arg alt'd GND (2X 3-5cm intervals, broken core)						
10	237.8-240.53	237.80	240.53	GND - Highly argillic-ser-+/- cb alt'd, lt gm-gy, appears wkly sheared wi arg/clay fract filling; no vis bt; local py fract filling (dk gy - black)		4		3	3	
				Possibly shr related vnlts - 80% py						
				Moderately hard dk brn mineral in py-qtz vn, no sph						
80	240.53-251.46	240.53	245.53	MSED; Upper contact somewhat irreg at 65 deg; mod'ly alt'd (ser); competent; pyritic shr vns in upper sample; at 28 deg to CA; at 90 deg to fol'n (70 deg); multiple py +/- cpy +/- aspy bearing vns in first 3m		3				1
				Irregular py/cpy/aspy stringer zone; appears to be intrusive, with small frags of MSED in sulphide mtx; moderately silicified; similar to prev though less min'n						
				No vis py stringers; multiple off wht qtz vns						
				Aspy + qtz + py vn at 150 deg relative to MSED fol'n at 50 deg; similar to sulphide veins in previous samples						
80		245.53	251.46	Relatively unaltered (hornfels?) MSED; MSED common foliation parallels qtz vns (pre-metam) at 50 deg with x-cutting qtz vns at 150 deg; At 246.54m MSED fol'n at 50 deg		1				
				MSED; dk brn gry at 50 deg to CA						
				MSED foliation at 80 deg at 248.9m						
				GND (mod arg/ser alt'd) at 250.21 - 250.3m and 250.57 - 250.63m; increasing se alt'n at EOH, no vis min'n						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048596 Return Samples
4	1	3.0	5.0	140		10.0	ser/cb/arg	3		0.5												B292958	233.17	234.60	**0.028**			VA05052041	1.43	
3	1	1.5	2.0	140		2.0	ser/cb/arg	3		25.0			0.8									B292959	234.60	235.58	**0.933**			VA05052041	0.98	
4	6	0.2	0.6	160		1.0	ser/arg/cb	3		60.0			1.0																	
5	1	0.7	4.0	60	70	3.0	ser/cb/arg	3		0.5												B292960	235.58	236.55	**0.025**			VA05052041	0.97	
7	1	0.7	6.0	60		3.0	ser	3		1.0												B292961	236.55	237.80	**0.094**			VA05052041	1.25	
1	6	2.5	2.5	60		3.0	qtz/ser	3		70.0			4.0																	
7	1	0.7	6.0	60		3.0	ser	3		1.0												B292962	236.55	237.80	**0.082**	DUP		VA05052041	1.25	
1	6	2.5	2.5	60		3.0	qtz/ser	3		70.0			4.0																	
10	1	2.0	8.0	70	160	10.0	arg/ser/cb	4		3.0			0.8									B292963	237.80	239.27	**0.011**			VA05052041	1.47	
3	6	0.1	1.0	70	160	0.5	arg/ser/cb	4		70.0			0.8																	
7	1	3.0	10.0	60		11.0	arg/ser/cb	4		3.0			1.0									B292964	239.27	240.79	**0.061**			VA05052041	1.52	
3	6	0.3	2.0	170		0.1	arg	4		80.0			1.0																	
5	1	0.8	3.0	60	70	10.0	arg/ser/cb	3		2.0			0.8									B292965	240.79	241.53	**0.066**			VA05052041	0.74	
1	6	0.5	0.5	50		1.0	ser/ch	3		3.0			3.0								5.0									
3	6	0.8	3.0	25		2.0	qtz/ser	3		55.0												B292966	241.53	242.16	**0.358**			VA05052041	0.63	
5	1	0.7	3.0	60		3.0	qtz/ser	3		0.6												B292967	242.16	243.10	**0.061**			VA05052041	0.94	0.548
3	6	3.0	6.0	30	40	5.0	qtz	3		25.0		15.0	20.0									B292968	243.10	243.54	**2.46**			VA05052041	0.44	
3	6	3.0	6.0	30	40	5.0	qtz	3		25.0		15.0	20.0									B292969	243.10	243.54	**2.45**	PD/CA	High Sulphides	VA05052041	0.44	
																						B292970	STANDARD 7G		**4.53**	7G		VA05052041		
3	6	0.3	1.2	40		4.0	qtz	3		20.0		2.0	5.0									B292971	243.54	243.84	**0.254**			VA05052041	0.30	
5	1	9.0	15.0	70		5.0	qtz/ser	3		0.8												B292972	243.84	244.60	**0.092**			VA05052041	0.76	
1	6	3.0	3.0	150		3.0	qtz	3		8.0			12.0									B292973	244.60	244.75	**1.055**			VA05052041	0.15	
7	1	0.5	3.0	150		0.5	qtz/ser	3		1.0												B292974	244.75	245.53	**0.067**			VA05052041	0.78	
8	1	1.0	6.5	150		0.3	qtz/ser	3		0.5												B292975	245.53	246.89	**0.008**			VA05052041	1.36	0.687
10	1	1.0	6.0	50																											
																						B292976	BLANK		**<0.005**			VA05052041		
5	1	0.7	4.0	137	140	1.0	ser	2		0.5												B292977	246.89	248.41	**0.014**			VA05052041	1.52	0.877
1	1	6.0	6.0	137		1.0	ser	2		6.0			1.0										(247.10	247.16)						
6	1	1.0	5.0	160		2.0	ser	2		0.5			0.2									B292978	248.41	249.94	**0.009**			VA05052041	1.53	0.836
1	1	10.0	10.0	80		0.5	ser	1		0.5													(249.4	249.5)						
5	1	3.0	6.0	80		10.0	ser	2		0.5												B292979	249.94	251.46	**<0.005**			VA05052041	1.52	0.755
2	1	0.5	1.0	155		1.0	ser/cb	3		0.5																				0.661
																						EOH								

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-283C

PROJECT: Dublin Gulch

GROUND ELEVATION: 998m

BEARING: 000 | DIP: -50°

DATE STARTED: 12-Jun-05 | DATE COMPLETED: 15-Jun-05

LOGGED BY: M. Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459704 NORTHING: 7099087

COORD SYSTEM: NAD 83: EASTING: 459585 NORTHING: 7099271

NAD 27 (CORRECTED for historic grid): EASTING: 459674 NORTHING: 7099097

SECTION LINE(historic grid): 459674E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: to 22.86m

Deviation:

Casing: 22.86m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
21.34	205.74	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B292034 to 292174

Requisition #: MASP448STRGOL.05Q | Date Shipped: 14-June-05

Lab Record #: VA05049843 | Date Received: 23-June-05

Sample Sequence: B292175 - B292214

Requisition #: MASP448STRGOL.05Q | Date Shipped: 21-June-05

Lab Record #: VA05051469 | Date Received: 29-June-05

Duplicates:	B292042, B292062, B292082, B292102, B292122, B292142, B292162, B292182, B292202
Preparation Duplicate/ Check Assay:	B292049, B292069, B292089, B292109, B292129, B292149, B292169, B292189, B292209
Standards:	B292050, B292070, B292090, B292110, B292130, B292150, B292170, B292190, B292210
Blanks:	B292036, B292056, B292076, B292096, 292116, B292136, B292156, B292176, B292196

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	340.5	50.2	6.5	7.5
150	341.2	49.5	7.2	8.2
205.74	342.5	48.1	8.5	9.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1			DATE: June 11-16th, 2005 PAGE 1 of 14							
DRILL HOLE # : DG05-283C			FeOx: 0 = Unoxidized, 5 = Intensely Ox'd; Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered; Carbonate: 0 = No Effervescence, 5 = Strong Effervescence							
Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 50; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93										
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 21.34			Casing (no recovery)						
10	21.34-205.76m	21.34	22.86	Extremely altered GND. Competent chunks up to 3cm diameter, oxidized through. sencite clay and argillic clay make up 80% of sample	5	4	2	4		
10		22.86	25.91	Extremely altered but coherent rock. purple hue suggests hematite content (up to 40%) Carbonate on veinlets close to parallel w/ C.A. Qtz eyes visible, remnant GND texture barely. sand size gouge section @ 23.6m (10cm wide)	5	4	2	1	1	
10		25.91	28.00	Oxidized GND. Colour light to med brown. 3cm gouge (clay) section with slickensides (mod strength) at 26.5m. Yellowish brown clay	5	3	2	1		
10		28.00	28.96	Same rock, but more clay alteration (30%). Highly altered and broken up GND. Breakage at parallel to CA - 10°	5	4	2	1	1	
10		28.96	31.29	Same as 25.91 to 28.00m, except gouge @ 29.85 (cm wide)	5	4	2	1	1	
10		31.29	32.00	May have once been one large qtz vein, chunky qtz pieces up to 4cm wide dominate the section. Gouge (clay to sand) section from 31.8 - 32.00	5	4	1	2		
10		32.00	34.05	Med to light brown GND. Original texture 90% overprinted and aphanitic	5	4	3	2		
10		34.05	35.05	Poor recovery here. Deep brown sandy alteration product makes rock very crumbly	4	2	3	1	1	
10		35.05	36.20	Extremely altered, but coherent rock. Veinlets show lim/calcite. Overall colour greyish dark brown w/ green (CHL) and orange (LIM) on veinlets w/ wide, pervasive selvages	4	2	3	1	1	
10		36.20	37.00	Poor recovery, same rock. Veinlets are everywhere, approach 20 per $10cm^2$	5	2	1	2		
10		37.00	38.10	Oxidized (limonized) selvage around qtz veins and lim veinlets separated by unaltered GND (up to 8cm across, uneven patches).	3	1	1			
10		38.10	42.67	Extremely altered GND. Gouge to crumbly gravel section. Competent zones (still highly oxidized), up to 8cm long	4	2	3	3	1	
10		42.67	44.25	Brown, coherent GND (as at 35.05 - 36.20m but w/ less chl) vein full of hematite, red, concretionary texture	4	2	1	2	1	
10		44.25	47.24	Altered to clay (appears as gouge, but no slickensides). and minor brecciated GND	4		1	4	1	
10		47.24	49.54	V. broken up core. Pieces avg 4cm. Lim staining pervasive. hematite w/in qtz veins and at margins to 15%	4	1	1	1	1	
10		49.54	50.44	Broken up, limonized rock, w/ minor clay	4		1	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
0																						B292034	21.34	22.86	**0.134**			VA050549843	1.52
0																						B292035	22.86	24.38	**0.062**			VA050549843	1.52
																						B292036	BLANK		**0.006**			VA050549843	
																						B292037	24.38	25.91	**0.034**			VA050549843	1.53
2	1	0.5	0.8	10	30		s	2	5	1.0								5.0				B292038	25.91	27.43	**0.036**			VA050549843	1.52
							q	4																					
1	1	0.5	0.5	20			s	2	5													B292039	27.43	28.00	**0.021**			VA050549843	0.57
							q	4																					
1	4	0.3	0.3				cb	3	5													B292040	28.00	28.96	**0.066**			VA050549843	0.96
3	1	0.5	1.2	60	30		s	3	5	0.1								1.0				B292041	28.96	30.48	**0.091**			VA050549843	1.52
							q	3																					
3	1	0.5	1.2	60	30		s	3	5	0.1								1.0				B292042	28.96	30.48	**0.06**	DUP		VA050549843	1.52
							q	3																					
4	1	1.0	3.0	60			q	3	5													B292043	30.48	31.29	**0.099**			VA050549843	0.81
1	1	20.0	20.0				q	3	5	7.0		0.1						5.0				B292044	31.29	32.00	**0.702**		Qtz pieces	VA050549843	0.71
							s	5																					
1	6	1.0	1.0	50						100.0								4.0											
2	1	0.5	0.8	60						1.0								4.0				B292045	32.00	33.53	**0.022**			VA050549843	1.53
4	1	0.5	2.0	80	45		chl	1		1.0								5.0				B292046	33.53	34.05	**0.863**			VA050549843	0.52
							q	4																					
							s	4																					
0																						B292047	34.05	35.05	**0.103**			VA050549843	1.00
5	1	1.0	3.5	60	50		s	4	5	4.0			3.0					4.0	4.0			B292048	35.05	36.20	**0.059**			VA050549843	1.15
							chl	2																					
							q	2																					
5	1	1.0	3.5	60	50		s	4	5	4.0			3.0					4.0	4.0			B292049	35.05	36.20	**0.056**	PD/CA		VA050549843	1.15
							chl	2																					
							q	2																					
																						B292050	STANDARD 7G		**4.7**	7G		VA050549843	
2	1	0.4	0.8	50			s	4	5	0.0												B292051	36.20	37.00	**0.036**			VA050549843	0.80
							chl	2																					
							q	2																					
4	1	1.0	3.0	50	65		s	4	5	2.0								5.0				B292052	37.00	38.10	**0.028**			VA050549843	1.10
							chl	2																					
							q	2																					
0																						B292053	38.10	39.62	**0.118**			VA050549843	1.52
2	1	0.3	0.6				s	4	5													B292054	39.62	41.15	**0.06**			VA050549843	1.53
							chl	2																					
							q	2																					
3	1	0.5	1.0	30	10		s	4	5	1.0								5.0				B292055	41.15	42.67	**0.212**			VA050549843	1.52
							chl	2																					
							q	2																					
1	4	0.5	0.5	30		0.5	cb	2		1.0								5.0											
							chl	1																					
																						B292056	BLANK		**<0.005**			VA050549843	
0																						B292057	42.67	43.47	**0.043**			VA050549843	0.80
0																						B292058	43.47	44.25	**0.025**			VA050549843	0.78
0																						B292059	44.25	45.52	**0.007**			VA050549843	1.27
0																						B292060	45.52	47.24	**0.12**			VA050549843	1.72
1	4	3.0	3.0	30			cb	2														B292061	47.24	48.77	**0.04**			VA050549843	1.53
							s	3																					
							chl	1																					
1	4	3.0	3.0	30			cb	2														B292062	47.24	48.77	**0.034**	DUP		VA050549843	1.53
							s	3																					
							chl	1																					
1	1	1.3	1.3	25			q	2		5.0			1.0					5.0				B292063	48.77	49.54	**0.057**			VA050549843	0.77
							s	3																					
							chl	1																					
2	1	1.1	2.2				q	2		3.0								5.0				B292064	49.54	50.44	**0.013**			VA050549843	0.90
							s	3																					

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 3 of 14											
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd		Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered						Carbonate 0 = No Effervescence 5 = Strong Effervescence			
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
10		50.44	53.34	V broken up core w/ limonite and calcite on fracture faces and limonite pervasive. Slickensides (med grade) on fracture face to 40° to CA, shown in sericite	4	1	1	1	2			
10		53.34	54.44	Area of granular GND w/ alt'n zones separated by unaltered zones up to 8cm in diameter. Massive aspy vein w/in qtz vein	2	1	1	1	1			
10		54.44	54.74	Clay zone. No evidence of fault or shear here, but upper and lower to it has slickensides. Limonite and carbonate clay.	5	1	1	4	3			
10		54.74	55.97	Lim/carb rich altered GND. Coherent, relict GND texture easily visible in qtz/bt, but overall, colour is yellowish brown. Qtz vein broken but still in situ in coherent core.	3		1	1	3			
10		55.97	57.91	Less alt'd here. Unaltered GND between selvages around veinlets of limonite	3		1		3			
10		57.91	60.96	Slickensides in oxidized py and sericite. Strong on fracture faces @ 45° and 30°. Moderate altered GND								
10		60.96	65.53	Unaltered GND (20%) separated by selvages of veinlets of lim/calcite (mod slickensides) and sulphide veins. Slickensides in ox. py. on fracture faces @ 45° and 30°, sand size and crumbly texture for 20% of section								
10		65.53	70.10	Lim-alt'd GND w/ calcite. Color is pale brown. Relict texture of GND (90%). Vnlets w/ lim/calc are random & irregular.	3	0	1	1	2			
10		70.10	71.20	Grades from lim-stained GND relict texture to completely alt'd & unrecognizable w/ qtz, chunky w/ vnlets of ox'd py, ~5% of sample.	4	1	1	1	2			
10		71.20	71.63	Clay/gravel texture. Lenses of black, alt'd bt.								
10		71.63	83.13	GND, highly alt'd to crumbly, mostly (80%) incompetent rocks. Lim & calc vnlets pervade the rock & weaken it. Overall color white, orange & brown. Black bt speckles. Vns exist as alt'd/broken lines of qtz chunks: rounded; associated w/ clay-like black lenses of ox'd py.	4	1	1	3	4			
10		83.13	87.80	Clean, unalt'd GND except for selvages around grey qtz vns & minor sericite throughout GND for part.	1	2	0	0	1			
10		87.80	100.58	Rock dominated by lim staining & calcitic selvage. GND texture relict beneath brown staining. Small unalt'd sections (<10cm) where vnlets are less frequent (only 8 per 10cm of core). Most sections vnlets >20/cm. Crumbly/sandy texture (50%), broken up core to pc's <10cm (50%). at 93-93.1m: a qtz-carb vn.	3	2	1	2	3			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
							chl	1																					
1	4	0.4	0.4	40																		B292065	50.44	51.82	**0.023**			VA050549843	1.38
1	1	2.0	2.0			10.0	q	4	5	5.0			1.0					5.0	3.0			B292066	51.82	53.34	**0.016**		Qtz pieces	VA050549843	1.52
							s	2																					
1	6	1.0	1.0	20		4.0	q	3					40.0									B292067	53.34	54.44	**0.18**			VA050549843	1.10
0																						B292068	54.44	54.74	**0.028**			VA050549843	0.30
0																						B292069	54.44	54.74	**0.029**	PD/CA		VA050549843	0.30
																						B292070	STANDARD 5E		**1.435**	5E		VA050549843	
1	3	0.6	0.6	30		1.0	q	2	4	2.0			15.0					4.0	1.0			B292071	54.74	55.97	**0.097**			VA050549843	1.23
							cb	2																					
1	1	1.0	1.0	20		4.0	q	3	4				0.1																
0																						B292072	55.97	56.59	**0.098**			VA050549843	0.62
0																						B292073	56.59	57.91	**0.067**			VA050549843	1.32
0																						B292074	57.91	59.44	**0.073**			VA050549843	1.53
2	6	2.0	4.0	60		4.0	q	3	1	5.0			1.0					4.0				B292075	59.44	60.96	**0.061**			VA050549843	1.52
							cb	2																					
																						B292076	BLANK		**<0.005**			VA050549843	
1	1	1.0	1.0	40		3.0	q	4		10.0			5.0					4.0				B292077	60.96	62.48	**0.064**			VA050549843	1.52
							s	2																					
1	1	0.5	0.5							5.0								5.0				B292078	62.48	63.00	**0.068**		Qtz piece	VA050549843	0.52
1	1	0.5	0.5	30		1.0	q	4	3													B292079	63.00	64.01	**0.021**			VA050549843	1.01
							s	2																					
4	1	0.5	2.0	40	50	4.0	q	4	4		5.0							5.0				B292080	64.01	65.53	**0.177**			VA050549843	1.52
							s	2																					
3	1	0.5	1.5	50		1.4	q	4		2.0			1.0					4.0	5.0			B292081	65.53	67.06	**0.193**			VA050549843	1.53
							cb	4																					
1	6	1.0	1.0	50									80.0						1.0										
3	1	0.5	1.5	50		1.4	q	4		2.0			1.0					4.0	5.0			B292082	65.53	67.06	**0.191**	DUP		VA050549843	1.53
							cb	4																					
1	6	1.0	1.0	50									80.0																
1	1	0.4	0.4	50		52.0				5.0								5.0				B292083	67.06	68.58	**0.046**		Selvage is entire sample	VA050549843	1.52
4	1	0.5	2.0	30		2.0	q	3	1	5.0								5.0				B292084	68.58	70.10	**0.162**			VA050549843	1.52
							cb	2																					
										5.0								5.0				B292085	70.10	71.20	**0.132**			VA050549843	1.10
0																						B292086	71.20	71.53	**0.476**			VA050549843	0.33
2	1	1.0	2.0	60						5.0								5.0				B292087	71.53	73.00	**0.19**			VA050549843	1.47
1	1	2.0	2.0							5.0								5.0				B292088	73.00	73.74	**0.218**			VA050549843	0.74
1	1	2.0	2.0							5.0								5.0				B292089	73.00	73.74	**0.226**	PD/CA		VA050549843	0.74
																						B292090	STANDARD 1A		**0.771**	1A		VA050549843	
2	1	1.0	2.0	70						5.0												B292091	73.74	74.68	**1.35**			VA050549843	0.94
0																						B292092	74.68	76.20	**0.088**			VA050549843	1.52
0																						B292093	76.20	77.72	**0.143**			VA050549843	1.52
3	1	1.2	3.2	35	50					0.1								5.0				B292094	77.72	79.26	**0.068**			VA050549843	1.54
1	1	1.0	1.0							1.0								5.0				B292095	79.26	80.77	**0.203**			VA050549843	1.51
																						B292096	BLANK		**<0.005**			VA050549843	
2	3	2.0	3.0	55						0.1								5.0				B292097	80.77	82.30	**0.069**			VA050549843	1.53
3	1	3.0	5.5	55						10.0								5.0				B292098	82.30	83.13	**0.047**			VA050549843	0.83
3	1	1.5	3.0	40		2.0	q	3			10.0							2.0				B292099	83.13	83.82	**0.036**			VA050549843	0.69
							s	3																					
4	1	2.3	5.1	40		4.5	q	3		1.0	10.0		3.0					1.0	4.0			B292100	83.82	85.34	**0.299**			VA050549843	1.52
							s	3																					
3	1	1.0	3.0	40		3.0	q	3		2.0	1.0		1.0					4.0	3.0			B292101	85.34	86.87	**0.222**			VA050549843	1.53
							s	3																					
3	1	1.0	3.0	40		3.0	q	3		2.0	1.0		1.0					4.0	3.0			B292102	85.34	86.87	**0.198**	DUP		VA050549843	1.53
							s	3																					
0																						B292103	86.87	87.80	**0.014**			VA050549843	0.93
0																													
2	1	1.0	2.0	40			s	2	4	0.1								3.0				B292104	87.80	88.39	**0.039**			VA050549843	0.59

DRILL LOG LEGEND - P1	DATE: June 11-16th, 2005	PAGE 5 of 14	
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMQN = 20; DIQR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		100.58	102.65	V. broken, unalt'd GND broken on lim microfracs at reg angles to CA: 40°/120°. Carbonitized section from 102.01-102.11m, w/ slickensides & a sheared-out appearance, trending to 60° to CA. V. white (sericite, carb) w/ slickensides defined in vnlet of mafics (alt bt?).	1	1	0	1	1	
10		102.65	103.63	V. broken core, lim near pervasive but ~2-5cm pc's, unalt'd in the centre.	2	2	0	1	1	
10		103.63	109.73	Carbonitized/sericitized GND. Selvages noted are in immediate proximity, if available. Carbonate appears in vns as well as throughout matrix of GND.	0	4	0	1	3	
10		109.73	112.78	Carb-ser alt'n to pervasive crumbly clay rich rock. Light grey-white shear zone. Slickensides (ser & alt bt) & aligned planar sericite throughout. Mafic lenses are dark grey clay & make up 50% of section; does not include py - too soft; none visible shear zone hits competent rock @ 50° to CA. No limonite.	0	4	0	4	3	
10		112.78	121.92	Minor alt'd GND. Slightly silicified & sericitized & carbonitized. GND texture for 90% of section where alt'n is, rock is more crumbly & white. V. minor limonite on 5% of section (end 1m). 4x3cm xenolith (mafic) f. grained diorite @ 115.70m few more ~1cm diameter throughout section (3). 2cm shear section combining pale beige gouge sand. Evidence of shear in mafic (dark grey clay) bands, movement appears to 90° to CA.	0	2	0	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cp = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
							q	2														B292105	88.39	89.92	**0.044**			VA050549843	1.53
3	1	2.0	4.0	50						1.0			5.0					5.0	3.0			B292106	89.92	91.44	**0.225**			VA050549843	1.52
2	1	1.5	2.5	50		2.0	q	2					4.0					1.0				B292107	91.44	92.71	**0.478**			VA050549843	1.27
							chl	1																					
							s	1																					
1	4	2.0		20		8.0	s	3	3	10.0								5.0				B292108	92.71	93.18	**0.164**			VA050549843	0.47
							q	2																					
							cb	3																					
1	4	2.0		20		8.0	s	3	3	10.0								5.0				B292109	92.71	93.18	**0.171**	PD/CA		VA050549843	0.47
							q	2																					
							cb	3																					
																						B292110	STANDARD 6F		**3.07**	6F		VA050549843	
3	1	2.0	5.0	40		3.0	q	3			5.0							4.0				B292111	93.18	94.49	**2.6**			VA050549843	1.31
							s	1																					
1	1	1.0	1.0	10		2.0	q	3	3				5.0						1.0			B292112	94.49	96.01	**0.438**			VA050549843	1.52
							s	3																					
1	1	1.0	1.0	30		2.0	q	4	3				2.0						1.0			B292113	96.01	97.54	**0.152**			VA050549843	1.53
							s	2																					
0																						B292114	97.54	99.06	**0.144**			VA050549843	1.52
3	1	0.5	1.5	45		2.0	q	4	1	7.0	1.0		5.0					4.0	5.0			B292115	99.06	100.58	**0.324**			VA050549843	1.52
							s	3																					
																						B292116	BLANK		**<0.005**			VA050549843	
3	1	0.5	1.5	45		1.0	q	3	1		5.0		1.0						3.0			B292117	100.58	102.11	**0.092**			VA050549843	1.53
							s	3																					
2	6	0.4	0.6	50	140	2.0	q	2		2.0	65.0	2.0						5.0				B292118	102.11	102.65	**0.116**			VA050549843	0.54
							s	1																					
2	1	2.0	4.0				q	2	4	1.0								5.0				B292119	102.65	103.63	**0.109**			VA050549843	0.98
							s	3																					
3	4	4.0	10.0	45		5.0	s	4			0.1		1.0						2.0			B292120	103.63	105.16	**0.069**			VA050549843	1.53
							cb	4																					
5	1	3.0	5.1	30		2.0	q	1		1.0	3.0							4.0				B292121	105.16	106.68	**0.152**			VA050549843	1.52
							chl	3																					
							s	3																					
5	1	3.0	5.1	30		2.0	q	1		1.0	3.0							4.0				B292122	105.16	106.68	**0.094**	DUP		VA050549843	1.52
							chl	3																					
							s	3																					
1	4	2.0	2.0	40																		B292123	106.68	108.20	**0.166**			VA050549843	1.52
3	1	2.0	5.0	70		3.0	q	3																					
							s	3																					
3	1	2.0	5.0	50		2.0	q	4		5.0								5.0				B292124	108.20	109.73	**0.134**			VA050549843	1.53
							s	3																					
																						B292125	109.73	111.25	**0.156**			VA050549843	1.52
																						B292126	111.25	112.78	**0.095**			VA050549843	1.53
3	1	1.0	2.5	30	45	1.0	q	3			8.0		2.0					1.0				B292127	112.78	114.30	**0.024**			VA050549843	1.52
											s	3.0																	
4	1	1.0	3.5	45		2.0	q	3		2.0	12.0	0.1						2.0				B292128	114.30	115.82	**0.017**			VA050549843	1.52
							s	1																					
1	2	1.5	1.5	25		0.5	q	2																					
4	1	1.0	3.5	45		2.0	q	3		2.0	12.0	0.1						2.0				B292129	114.30	115.82	**0.018**	PD/CA		VA050549843	1.52
							s	1																					
1	2	1.5	1.5	25		0.5	q	2																					
																						B292130	STANDARD 7G		**4.15**	7G		VA050549843	
2	1	0.4	0.8	25																		B292131	115.82	117.35	**0.07**			VA050549843	1.53
1	1	1.0	1.0	60		1.0	q	1			5.0																		
1	1	1.0	1.0	40		1.0	q	1			2.0											B292132	117.35	118.87	**0.028**			VA050549843	1.52
							s	1																					
2	1	1.0	2.0	40		0.5	q	1			1.0							2.0				B292133	118.87	120.40	**0.009**			VA050549843	1.53
							s	1																					
2	1	1.0	2.0	50		1.0	q	1		1.0	5.0							2.0				B292134	120.40	121.92	**0.038**			VA050549843	1.52

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 7 of 14		
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		121.92	135.64	V. minor alt'd GND. Slightly more mafic in appearance. Vnlets, infrequent, of calcite infrequent 1 or 2/m of qtz w/ po. no (<1%) limonite. small xeno @ 124.5m, long axis parallel to qtz vn (40° to CA). 3x1cm. Reg breakage @ 30 & 80° to CA. Mod mineral slickensides on 30° faces, bt or dark sericite (soft, micaceous). 90% of qtz vns are grey qtz in the centre, w/ silicified zones surrounding. @ 133.6-135.64m: parallel to CA fracs break core lengthwise (2, mainly).	0	1	0	0	1	
10		135.64	139.59	Minor alt'd GND. Selvages around fracs & xenoliths account for alt'n. Slickensides in sericite/chlorite on frac faces @60° to CA.	0	1	1	0	0	
10		139.59	147.51	V. minor alt'd GND (carb), w/ large qtz vns (8cm max), small selvages. Xeno's up to 15x8cm (@142.2m) in size.	0	1	1	0	1	
				Cube (1cm^2) of qtz surrounded by 4mm selvage of chlorite @141.9m.						
				At 144.38m, nice, 1-2mm cpy. Slickensides on fractures @20-40° to CA increase in strength toward end of sample						
10		147.51	148.20	Fault zone. Crumbly gouge to gravel (brecciated GND). Contacts unalt'd GND at 20° (upper) & 35° (lower) w/ nice sericite slickensides.	1	3	2	3	3	
10		148.20	151.69	Carbonitized GND. Calcite in vnlets & through matrix of GND, making its texture crumbly & granular. Overall, color is whitish pale grey.	1	2	1	0	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. Stale 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							s	1																					
4	1	1.0	4.0	30	45	1.5	s	3		1.0	9.0							2.0				B292135	121.92	123.44	**0.012**			VA050549843	1.52
							q	3																					
																						B292136	BLANK		**<0.005**			VA050549843	
6	1	0.5	3.0	40		0.5	q	3		2.0			1.0									B292137	123.44	124.97	**0.046**			VA050549843	1.53
							s	3																					
5	1	1.0	5.0	45			q	3		2.0			1.0									B292138	124.97	126.49	**0.06**			VA050549843	1.52
							s	3																					
4	1	2.0	4.0	30	40	3.0	q	3			5.0		4.0					3.0	1.0			B292139	126.49	128.02	**0.011**			VA050549843	1.53
							s	2																					
							chl	2																					
0																						B292140	128.02	129.54	**0.057**			VA050549843	1.52
2	1	0.4	0.8	80	30	1.0	q	3			2.0							4.0				B292141	129.54	131.06	**0.012**			VA050549843	1.52
							s	2																					
2	1	0.4	0.8	80	30	1.0	q	3			2.0							4.0				B292142	129.54	131.06	**0.026**	DUP		VA050549843	1.52
							s	2																					
5	1	1.0	4.0	40		1.0	q	4			8.0							2.0				B292143	131.06	132.59	**0.066**			VA050549843	1.53
							s	2																					
0																						B292144	132.59	134.11	**0.006**			VA050549843	1.52
2	1	2.0	3.0	40	50	1.5	q	3			8.0		3.0					1.0	5.0			B292145	134.11	135.64	**0.018**			VA050549843	1.53
							s	3																					
5	1	2.3	5.0	40	50	1.0	q	3	0	0.1	3.0		4.0					5.0	4.0			B292146	135.64	137.16	**0.088**			VA050549843	1.52
							chl	1																					
							s	1																					
5	1	0.5	2.5	45		1.5	q	4			1.0		10.0						4.0			B292147	137.16	138.68	**0.04**			VA050549843	1.52
							chl	1																					
							s	2																					
1	1	0.5	0.5	40		2.0	q	2		10.0								2.0				B292148	138.68	139.59	**0.02**			VA050549843	0.91
							chl	3																					
							s	2																					
1	1	0.5	0.5	40		2.0	q	2		10.0								2.0				B292149	138.68	139.59	**0.021**	PD/CA		VA050549843	0.91
							chl	3																					
							s	2																					
																						B292150	STANDARD 3C		**0.082**	3C		VA050549843	
2	1	1.0	2.0	40		1.0	q	2		5.0								1.0				B292151	139.59	140.21	**0.093**			VA050549843	0.62
							chl	3																					
							s	2																					
4	1	1.3	4.0	40		2.0	q	4		5.0								2.0				B292152	140.21	141.73	**0.012**			VA050549843	1.52
							chl	1																					
							s	1																					
2	1	1.0	1.5	20	30	4.0	q	5	0	1.0								5.0				B292153	141.73	143.26	**0.013**			VA050549843	1.53
3	1	3.0	5.0	45		6.0	q	3	1		10.0	2.0						2.0				B292154	143.26	144.78	**0.162**			VA050549843	1.52
							chl	3																					
							s	2																					
2	1	6.0	8.0	20		2.0	q	3	0		10.0							2.0				B292155	144.78	146.30	**0.043**			VA050549843	1.52
							chl	3																					
							s	2																					
																						B292156	BLANK		**<0.005**			VA050549843	
2	1	1.0	2.0	30	10	4.0	q	3	0		8.0		4.0					2.0	2.0			B292157	146.30	147.51	**0.108**			VA050549843	1.21
							chl	3																					
							s	2																					
0																						B292158	147.51	148.20	**0.022**			VA050549843	0.69
3	3	2.5	6.5	20	30	5.0	q	3	1		5.0		3.0					1.0	3.0			B292159	148.20	148.87	**0.08**			VA050549843	0.67
							cb	3																					
							s	3																					
1	1	1.3	1.3	50		4.0	q	3			2.0		2.0					0.0	0.0										
							chl	3																					
							s	2																					
0																						B292160	148.87	149.35	**0.028**			VA050549843	0.48
4	1	2.0	4.5	50		6.0	q	3			15.0		1.0					1.0	3.0			B292161	149.35	150.88	**0.046**			VA050549843	1.53
							chl	3																					

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005	PAGE 9 of 14	
DRILL HOLE # : DG05-283C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		151.69	154.68	Mod'ly alt'd GND. Calcite-infused from vnlets & through matrix.	0	3	2	0	2	
10		154.58	156.74	Carb & chl & ser-alt'd GND. Crumbly gravel to sandy texture. GND texture 90% erased. Weak slickensides on irregular frac faces, in alt'd bt & ox'd py. General trend to these black lenses is 45° to CA. Color is minty green w/ grey & white patches.	0	4	3	1	3	
10		156.74	157.32	Sample is 75% pure qtz & carb (vn) & 30% carbonitized GND selvage, all quite crumbly.	0	1	0	1	4	
10		157.32	158.82	One huge (150cm) qtz/carb vn. 5% sulphides (half oxidized) disseminated throughout. Quite soft (5) & crumbly, opaque white.	0	0	0	0	4	
10		158.82	166.82	Mod'ly alt'd GND. Broken up to ~10cm chunks avg. Grey qtz vns w/ irregular edges & no real orientation. From 162-162.5m: low angle grey qtz vn appears folded. Lack of selvage also suggests post-vn mmphsm/ 2nd intrusion/ degree of heat to reset GND as unalt'd. Selvages relation to vn size is cryptic. Next small vn has large selvage (diff comp - may be part of later vein episode).	0	2	1	0	2	
10		166.82	169.99	Section dominated by large qtz/carb vns (1.03m & 1.46m wide). 3.17m total, 2.49m vn at 168.35m, (40cm section btwn >1m vns), one small selvage has ox'd py smeared onto frac face; treated as vn even though it has obviously been sheared.	0	1	1	0	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							s	2																					
4	1	2.0	4.5	50		6.0	q	3			15.0		1.0					1.0	3.0			B292162	149.35	150.88	**0.046**	DUP		VA050549843	1.53
							chl	3																					
							s	2																					
4	1	1.0	4.0	50		8.0	q	3			5.0							1.0				B292163	150.88	151.69	**0.172**			VA050549843	0.81
							chl	3																					
							s	2																					
5	1	1.0	4.0	45		3.0	q	3	0		5.0											B292164	151.69	152.40	**0.099**			VA050549843	0.71
							chl	1																					
							s	4																					
							cb	1																					
6	1	1.0	4.0	45		2.0	q	3	0		7.0											B292165	152.40	153.92	**0.009**			VA050549843	1.52
							chl	1																					
							s	4																					
							cb	1																					
3	1	1.0	2.0	45		10.0	q	2	0		1.0											B292166	153.92	154.58	**0.012**			VA050549843	0.66
							chl	3																					
							s	2																					
							cb	1																					
5	1	1.0	4.5	60	20		q	1	0	10.0								4.0				B292167	154.58	155.62	**0.257**			VA050549843	1.04
							chl	4																					
							s	4																					
							cb	2																					
2	1	2.0	4.0	50			q	1	0	4.0								4.0				B292168	155.62	156.74	**0.063**			VA050549843	1.12
							chl/s	4																					
							cb	2																					
2	1	2.0	4.0	50			q	1	0	4.0								4.0				B292169	155.62	156.74	**0.069**	PD/CA		VA050549843	1.12
							chl/s	4																					
							cb	2																					
																						B292170	STANDARD 7G		**4.36**	7G		VA050549843	
2	3	20.0	22.0	30			q	3	1	3.0			2.0					2.0	0.0			B292171	156.74	157.32	**0.055**			VA050549843	0.58
							cb	4																					
							s	2																					
1	3	150.0	150.0	50		0.0				3.0			2.0					4.0	2.0			B292172	157.32	158.82	**0.042**		Selvage not incl. in sample (only vn).	VA050549843	1.50
0																						B292173	158.82	160.02	**0.013**			VA050549843	1.20
2	1	1.5	2.5	30	65	3.0	q	3		3.0			1.0					4.0				B292174	160.02	161.54	**0.016**			VA050549843	1.52
							chl	3																					
3	1	4.0	9.0	10		1.0	q	2		0.0												B292175	161.54	163.07	**0.012**			VA05051469	1.53
							chl	4																					
																						B292176	BLANK		**<0.005**			VA05051469	
1	1	1.0	1.0	25		2.0	q	3					10.0						3.0			B292177	163.07	164.59	**0.015**			VA05051469	1.52
							chl	2																					
3	1	1.0	3.0	30		20.0	q	3			12.0	1.0	0.1					0.0	0.0			B292178	164.59	166.82	**0.049**			VA05051469	2.23
							chl	3																					
							s	2																					
							cb	2																					
1	3	6.0	6.0	10		3.0	q	3	0	3.0			2.0						2.0										
							cb	1																					
							s	1																					
							chl	2																					
1	3	103.0	103.0	30		16.0	q	2	0	8.0	1.0		2.0					4.0	1.0			B292179	166.82	168.18	**0.08**		Selvages included	VA05051469	1.36
							chl	4																					
							s	2																					
							cb	2																					
1	3	1.0	1.0	50		8.0	q	2	0	10.0								4.0				B292180	168.18	168.71	**0.014**			VA05051469	0.53
							chl	4																					
							s	2																					
							cb	2																					
1	3	128.0	128.0	60		0.0				5.0	1.0		1.0					4.0	3.0			B292181	168.71	169.99	**0.017**		Selvage not incl.	VA05051469	1.28
1	3	128.0	128.0	60		0.0				5.0	1.0		1.0					4.0	3.0			B292182	168.71	169.99	**0.01**	DUP		VA05051469	1.28

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		169.99	183.82	Minor carb alt'n around qtz/carb vns & through vnlets. Otherwise v. minorly alt'd GND.	0	1	1	0	2	
10		183.82	184.80	Beginning gradation to heavily chloritized GND. Half of sample is v. alt'd w/ ser & chl. Unalt'd GND appears v. mafic (qtz <20%) w/ milky qtz vns.	0	3	3	0	1	
10		184.80	185.93	70% alt'd GND here. Appears in bands, selvage around qtz/carb vns.	0	2	4	0	2	
10		185.93	187.45	Crumbly, carb-rich, highly chloritized rock. No evidence of shear.	0	2	4	2	3	
10		187.45	205.26	GND chl'd. Color medium teal green to deep greenish grey. Reg fracs at 60-70° to CA. Smooth appearance, aphanitic. Med-sized qtz vns (~2-3/m) run through entire section. Vnlets of calcite are also frequent (~20/m), at 60° & 0° to CA. Qtz vns have a varying amount of calcite w/in them, from 0-90% - noted per sample on 2nd page: if calcite <50%, it is considered a "1", if >50%, "3"-type vein. @ 202.00-202.69m: a banded section w/ ox'd py in chunks to vnlets surrounds broken & rounded qtz vns.	0	2	5	0	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotitie	other		From	To					
1	1	3.0	3.0	55		0.5	q	5	0	0.0												B292183	169.99	170.69	**0.005**			VA05051469	0.70
8	1	2.0	5.5	30	55	2.0	q	3		2.0	8.0	1.0						4.0				B292184	170.69	172.21	**1.995**			VA05051469	1.52
							chl	3																					
							s	1																					
							cb	1																					
1	3	1.0	1.0	45		6.0	q	2			3.0		10.0						3.0			B292185	172.21	173.74	**0.014**			VA05051469	1.53
							chl	3																					
							s	1																					
							cb	3																					
7	1	1.0	3.0	50	10	2.0	q	3	0	3.0	8.0		10.0					3.0	2.0			B292186	173.74	175.26	**0.046**			VA05051469	1.52
							s	2																					
5	1	1.0	2.0	50	20	1.0	q	3	0	5.0			10.0					0.0	3.0			B292187	175.26	176.78	**0.019**			VA05051469	1.52
							s	2																					
5	1	3.0	5.0	50		1.0	q	3	0	3.0			5.0					0.0	3.0			B292188	176.78	178.31	**0.022**			VA05051469	1.53
							s	2																					
5	1	3.0	5.0	50		1.0	q	3	0	3.0			5.0					0.0	3.0			B292189	176.78	178.31	**0.017**	PD/CA		VA05051469	1.53
							s	2																					
																						B292190	STANDARD 1A		**0.861**	1A		VA05051469	
3	1	4.0	8.5	40	50	8.0	q	3			10.0		5.0						1.0			B292191	178.31	179.83	**0.009**			VA05051469	1.52
							s	2																					
6	1	2.0	7.0	60	30	5.0	q	3			2.0		2.0						3.0			B292192	179.83	181.36	**0.008**			VA05051469	1.53
							s	2																					
							chl	3																					
5	1	1.0	5.0	45		4.0	q	3			6.0		4.0					0.0	0.0			B292193	181.36	182.88	**0.052**			VA05051469	1.52
							s	2																					
							chl	2																					
3	1	1.5	3.0	40		2.0	q	3					5.0						3.0			B292194	182.88	183.82	**0.024**			VA05051469	0.94
							s	3																					
							chl	2																					
4	1	1.0	2.5	30		2.0	q	3	0		3.0		1.0						3.0			B292195	183.82	184.80	**0.083**			VA05051469	0.98
							chl	2																					
							s	3																					
																						B292196	BLANK		**<0.005**			VA05051469	
6	3	0.5	2.5	40	50	8.0	q	1		5.0								5.0				B292197	184.80	185.93	**0.111**			VA05051469	1.13
							chl	4																					
							s	3																					
							cb	2																					
4	1	5.0	16.0	60	30		chl	4					3.0						3.0			B292198	185.93	187.45	**0.123**			VA05051469	1.52
							s	2																					
							cb	2																					
3	1	5.5	13.0	55			chl	4		8.0	2.0		1.0					3.0	1.0			B292199	187.45	188.98	**0.643**			VA05051469	1.53
							s	2																					
							cb	2																					
2	3	1.0	1.5	55																									
4	1	0.5	2.0	50			chl	4		3.0			1.0					4.0	3.0			B292200	188.98	190.50	**1.115**			VA05051469	1.52
							s	2																					
							cb	2																					
1	3	0.5	0.5	50			chl	4		1.0								5.0											
							s	2																					
							cb	2																					
3	1	3.5	9.5	50			chl	4					4.0						2.0			B292201	190.50	192.02	**0.43**			VA05051469	1.52
							s	2																					
							cb	2																					
3	1	3.5	9.5	50			chl	4					4.0						2.0			B292202	190.50	192.02	**0.248**	DUP		VA05051469	1.52
							s	2																					
							cb	2																					
3	1	3.0	6.0	50			chl	4		3.0			1.0					4.0	4.0			B292203	192.02	193.55	**0.061**			VA05051469	1.53
							s	2																					
							cb	2																					
2	3	0.5	1.0	50						0.0																			
4	1	2.0	4.5	50			chl	4		5.0			2.0					1.0	1.0			B292204	193.55	195.07	**0.127**			VA05051469	1.52
							s	2																					

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 13 of 14	
DRILL HOLE # : DG05-283C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		202.69	204.22	Interesting vns; all are 1cm width, one qtz vn is folded & sheared (brittle ductile, see picture). Carb vns are overprinted & moved by qtz vns in some places. Look partially syn-intrusive because of appearance of both w/in small areas & mixing btwn the 2 in most vns.						
				Last 18cm of section 205.08-205.26m is grading out of chloritic section. Appears as selvage, more granular texture, more GND-ish.						
10		205.26	205.74	Still somewhat chl'd but GND texture visible again & color is deep greenish grey.	0	2	2	0	0	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							cb	2																					
1	3	3.0	3.0	50			chl	4		3.0								2.0											
							s	2																					
							cb	2																					
4	1	4.0	12.0	50			chl	4		13.0	3.0							2.0				B292205	195.07	196.60	**0.193**			VA05051469	1.53
							s	2																					
							cb	2																					
5	1	2.0	4.0	55			chl	4		7.0			1.0					4.0				B292206	196.60	198.12	**0.138**			VA05051469	1.52
							s	2																					
							cb	2																					
5	1	4.0	11.0	55						6.0	4.0							4.0				B292207	198.12	199.64	**0.565**			VA05051469	1.52
5	1	5.0	9.0	55						3.0	1.0							4.0				B292208	199.64	201.17	**2.82**			VA05051469	1.53
5	1	5.0	9.0	55						3.0	1.0							4.0				B292209	199.64	201.17	**3**	PD/CA		VA05051469	1.53
																						B292210	STANDARD 4D		**1.56**	4D		VA05051469	
4	1	2.0	8.0	55						20.0								5.0				B292211	201.17	202.69	**0.381**			VA05051469	1.52
3	6	1.0	2.0	55		0.0				95.0	5.0							5.0											
6	1	1.0	6.0	50	60		chl	4		2.0								1.0				B292212	202.69	204.22	**0.323**			VA05051469	1.53
							s	2																					
							cb	2																					
3	3	1.0	3.0	50			chl	4		1.0								5.0											
							s	2																					
							cb	2																					
8	1	2.5	7.5	65	50		chl	4		5.0								3.0				B292213	204.22	205.26	**0.324**			VA05051469	1.04
							s	2																					
							cb	2																					
1	1	1.0	1.0	60		6.0	q	1	0	3.0	1.0							5.0				B292214	205.26	205.76	**0.353**			VA05051469	0.50
							chl	3																					
							s	3																					
							cb	1																					
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-284C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 865m

BEARING: 000 | DIP: -50°

DATE STARTED: 15-Jun-05 | DATE COMPLETED: 17-Jun-05

LOGGED BY: Terry Croteau & Kristian Whitehead

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459105 NORTHING: 7099382

COORD SYSTEM: NAD 83: EASTING: 458987 NORTHING: 7099570

NAD 27 (CORRECTED for historic grid): EASTING: 459075 NORTHING: 7099392

SECTION LINE 459075 (historic grid)

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 10.67m

Deviation:

Casing: 10.67m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B292980-B293000 and B380201-B380246

Requisition #: MASP448STRGOL.05Q | Date Shipped: 21-June-05

Lab Record #: VA05052040 | Date Received: 30-June-05

Sample Sequence: B380247-B380300

Requisition #: MASP448STRGOL.05Q | Date Shipped: 24-June-05

Lab Record #: VA05054218 & VA05053956(301-306) | Date Received: 05-July-05

Sample Sequence: B290356-B290387 (returns)

Requisition #: MASP448STRGOL.05Q | Date Shipped: 24-June-05

Lab Record #: VA05053955 | Date Received: 04-July-05

Duplicates: B292982, B380202; B380222; B380242; B380262; B380282; B380302

Preparation Duplicate/ Check Assay: B292989; 380209; 380229; 380249; 380269; 380289

Standards: B292990 (3C); B380210 (4D); B380230(1A); B380250 (6F); B380270 (6F); 380290 (3C)

Blanks: B292996; B380216; B380236; B380256; B380276; B380296

FROM	TO	LITHOLOGY
10.67	107.40	MSED - ARGL w/ QZZ layers
107.40	114.83	GND
114.83	134.71	MSED - ARGL w/ QZZ layers
134.71	135.72	GND
135.72	138.68	MSED - ARGL w/ QZZ layers

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
50	341	-51.7	007	008
67.06	341.5	-52	007.5	008.5
100	342	-53.9	008	009
138.68	342.1	-54.7	008.1	009.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 1 of 6								
DRILL HOLE # : DG05-284C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered				**Carbonate** 0 = No Effervescence 5 = Strong Effervescence				
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93										
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-10.67	0.00	10.67	Casing (No core recovered)						
80	10.67-18.29	10.67	18.29	MSED: Meta sediments (argillite) , foliations are mm scale w/ foliations at 10-11 metres at 60 ° wi limonite semi pervasive on foliation; lim predominant on fractures. Core is black with minor qtz boudins and stringers, no sulphides present at surface. Not silicified (scratches with nail).	3					
12	18.29-19.30	18.29	19.30	GNDD (Granodiorite Dike), upper contact not vis. Broken core, qtz vn wi dissem aspy (tr) pieces; lower ctc at 60-65°		2		3		
80	19.3-21.54	19.30	21.54	Meta-Sediments; very broken core; Foliation at 40-50°; GND vein at 40° (7cm); qtz veins at 90° to GND dike at 20° (or 155°) TCA; trace diss aspy; GND intruded metaseds parallel to foliation at 40° TCA						
10	21.54-22.49	21.54	22.49	GND; broken core; sections of bleached GND with sulphides and quartz veinlets		2		3		
80	22.49-57.91	22.49	57.91	MSED; Foliation at 0° or parallel to CA; upper contact at 40° TCA						
				At 24.47m MSED's become silicified and core badly broken						
				At 27.43m recovery increases; Foliations and crenulations at 45° TCA to as steep as 85° TCA at 30.78m						
80		35.05	36.58	MSED foliation at 45° TCA; hematite on fracture surfaces; veinlets running at 45° TCA contain trace cpy in vein; At 35.56 3 cm GND dyke at 40° TCA; broken qtz vn present with weathered aspy						
80		36.58	38.10	MSED; Foliation to 0 ° TCA and becomes crenulated; changes to 30 ° TCA at 37.62m; Sheeted vn set at 37.06m at 40 ° TCA (3 0.5 cm qtz vns)						
80		38.10	39.62	MSED; Good recovery; lim on fracture surfaces; Foliation at 70° to 45° TCA at 38.3m						
80		39.62	42.34	MSED; Foliation at 50 ° TCA; Core becomes darker (more arg?) and broken; Recovery decreases, becoming very poor (30% at 41.15m)						
				At 40.20m - 3 cm and 4 cm qtz veins; grey qtz at 60° TCA; trace aspy; gravel sized MSED at 42.04m						
80		42.34	43.30	Core becomes bleached (silicified) and contains 10 - 15% subhedral aspy and 5% py; at 42.95m core becomes gougy; small qtz pieces and argillite present in gouge; gouge to 7cm at 45° TCA						5
80		43.30	44.50	Poor core recovery; core is commonly reduced to gravel size or smaller pieces (<1.5cm); broken qtz vns are present in gravel; solid pieces of core show lineations @85° TCA						
80		44.50	50.29	Foliation at 85° TCA; trending to 50° at 46.84m; Heavy limoninte staining in fractures; Core recovery is good; At 49.59m, 18cm bleached, silicified section related to 3cm qtz vein.						
		50.29	51.82	Core is silicified and intruded by bleached GND dykes (3cm) dykes cut through 1cm qtz vein; hem staining absent; MSED becomes fragmented into gravel size pieces; core recovery becomes very poor						
		51.82	54.86	Core recovery poor; numerous vnlts throughout; Foliation continues at 45-50 °; often crenulated						
		54.86	56.39	Core is dark green, chloritized (?); Euhedral aspy crystals disseminated throughout; Gouge at 54.16m (5cm); qtz eyes; core becomes black (argillite) with foliation at 50° TCA			4			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						Casing	0.00	10.67					
																						B292980	10.67	12.19	0.006			VA05052040	1.52
										1.0												B292981	12.19	13.72	0.019		V. minor qtz pieces; Py on frac surface	VA05052040	1.53
										1.0												B292982	12.19	13.72	0.011	DUP		VA05052040	1.53
																						B292983	13.72	15.24	0.017		Very poor core recovery	VA05052040	1.52
1	1	35.0	35.0										0.1									B292984	15.24	16.76	0.015			VA05052040	1.52
																						B292985	16.76	18.29	0.051		Very poor core recovery	VA05052040	1.53
1	1												0.1									B292986	18.29	19.81	0.041			VA05052040	1.52
3	1	0.75	1.0	40	20								0.1									B292987	19.81	21.34	0.023			VA05052040	1.53
	2	0.5	1.0	20		20.0		2	1	0.1			0.1					4.0				B292988	21.34	22.26	0.011			VA05052040	0.92
	2	0.5	1.0	20		20.0		2	1	0.1			0.1					4.0				B292989	21.34	22.26	0.011	PD/CA		VA05052040	0.92
																						B292990	STANDARD 3C		0.098	3C		VA05052040	
																						B292991	22.26	22.49	0.006		Nothing Significant	VA05052040	0.23
1	1	0.25	0.25	20		0.0																B292992	22.49	23.95	0.010			VA05052040	1.46
3	1	5.0	5.5	30	35								0.1									B292993	23.95	24.47	0.006			VA05052040	0.52
																						B292994	24.47	25.91	0.008		1, 3.5 cm quartz piece	VA05052040	1.44
																						B292995	25.91	27.43	0.007		Quartz pieces, no visible sulphides	VA05052040	1.52
																						B292996	BLANK		<0.005			VA05052040	
3	1	0.5	1.0	20	30																	B292997	27.43	28.96	<0.005			VA05052040	1.53
2	1	0.5	1.0	30																		B292998	28.96	30.48	<0.005			VA05052040	1.52
2	1	0.25	0.5	60																		B292999	30.48	32.00	<0.005			VA05052040	1.52
																						B293000	32.00	33.53	0.008			VA05052040	1.53
																						B380201	33.53	34.42	0.006			VA05052040	0.89
																						B380202	33.53	34.42	0.006	DUP		VA05052040	0.89
																						B380203	34.42	35.05	0.013			VA05052040	0.63
4	1	1.0	2.5	45		0.0							0.1									B380204	35.05	36.58	0.007			VA05052040	1.53
8	1	1.0	2.5	40		0.0							10.0						3.0			B380205	36.58	38.10	0.018			VA05052040	1.52
3	1	0.2	0.6	40	10	0.2	q	3	1				5.0									B380206	38.10	39.62	0.010			VA05052040	1.52
2	1	4.0	7.0	60		0.0							0.1									B380207	39.62	40.47	0.011			VA05052040	0.85
2	1	0.5	0.7	40									1.0									B380208	40.47	41.15	0.007			VA05052040	0.68
2	1	0.5	0.7	40									1.0									B380209	40.47	41.14	0.007	PD/CA		VA05052040	0.67
																						B380210	STANDARD 4D		0.469	4D		VA05052040	
																						B380211	41.15	42.34	0.038			VA05052040	1.19
																						B380212	42.34	43.30	0.196			VA05052040	0.96
2	1	0.3	0.6	30									10.0									B380213	43.30	44.50	0.017			VA05052040	1.20
																						B380214	44.50	45.72	0.009			VA05052040	1.22
2	1	2.0	5.0	70		0.0							2.0									B380215	45.72	47.24	0.010			VA05052040	1.52
																						B380216	BLANK		<0.005			VA05052040	
2	1	0.3	0.5	35		0.2	q	2	0				10.0						60.0			B380217	47.24	48.79	0.006			VA05052040	1.55
5	1	2.0	2.8	20		0.0							3.0						10.0			B380218	48.79	49.59	0.013			VA05052040	0.80
3	1	3.0	8.0	30		5.0	q	5	0	5.0			10.0						70.0			B380219	49.59	50.29	0.021			VA05052040	0.70
5	1	2.0	7.0	30		4.0	q	5	0	10.0			15.0					90.0	10.0			B380220	50.29	51.82	0.014			VA05052040	1.53
4	1	1.0	1.8	30		0.0							10.0						30.0			B380221	51.82	53.34	0.021			VA05052040	1.52
4	1	1.0	1.8	30		0.0							10.0						30.0			B380222	51.82	53.34	0.008	DUP		VA05052040	1.52
3	1	3.0	5.0	40		2.0	q	5	0	20.0			5.0					1.0				B380223	53.34	54.86	0.008			VA05052040	1.52
4	1	3.0	3.6	70		0.0				10.0			10.0									B380224	54.86	56.39	0.037			VA05052040	1.53

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 3 of 6		
DRILL HOLE # : DG05-284C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
		56.39	57.91	Core becomes clay rich and altered; Recover is very poor (32%); QZZ starts to appear as frags at 57.60m; contact btw QZZ and MSEDs not visible						
70	57.91-67.45	57.91	67.45	Quartzite (QZZ) - Fine grained; Pyrite on some fractures; disseminated and aspy also present diss throughout; veinlets carry abndt aspy; Recovery good (75%)						
80	67.45-72.10	67.45	71.33	MSED with foliation angles at 60° TCA; diss py and aspy present throughout; At 67.98m 5 cm gouge at 60°; At 70.77m 4cm gg at 70° TCA; foliation is crenulated 69.65 to 69.85m						
		71.33	72.10	Metaseds more silicified; Quartzite? Clayey gouge at 71.43m, 6cm, at 60° TCA; At 71.81m a 5cm grey quartz vein, fractured, at 80° TCA.						
70	72.10-76.20	72.10	73.15	QZZ/MSED ctc; interbedded through interval; At 73.05m 10cm grey qtz vein at 45° TCA						
70		73.15	76.20	QZZ; Good rec, diss aspy throughout; sulphide veinlets at 75.36 to 75.45m						
80	76.20-76.90	76.20	76.90	MSED; Foliation at 60°; high silicic alteration; At 76.25m a 7cm qtz vein; vugs present, possibly due to weathering out of sulphides						
70	76.90-78.42	76.90	78.42	QZZ; Sulphide veinlets (py) present; 11cm vein at 77.92m; vugs with weathered aspy present						
80	78.42-85.34	78.42	82.30	MSED; Foliation at 65-70° TCA throughout; MSEDS are altered heavily around selvages via silica or chlorite; at 81.95m 9cm clayey gouge qtz and MSED frags.						
		82.30	85.34	MSEDS black with foliation at 50° TCA; at 82.51m to 82.76m altered to clay; very micaceous; Diss aspy and po present; Euhedral aspy crystals present on some fractures						
70	85.34-107.40	85.34	90.62	QZZ; Transitions from MSED to QZZ' initial foliations at 60° reducing after 86.05m to absent by 88.39m; Initially core is broken, becoming more competent as QZZ more dominant at 88.05m						
70		90.62	92.96	QZZ with interbedded MSED; MSED black and micaceous (biot) to argillic; no visible foliation in MSEDS at 50° TCA; Core is broken; At 92.08m 6cm clayey gouge at 50° TCA; Diss py in gouge; Qtz eyes						
70		92.96	96.75	QZZ; Good core rec; diss py present; vugs filled wi py						
70		96.75	103.13	QZZ with interbedded MSED; Recovery decreases; Foliations at 45° where vis; often crenulated; Qtz stringers running at 30° TCA contain aspy.						
70		103.13	107.40	QZZ; Carbonate present on most fractures; occasionally found wi py on top of slickenslides; numerous vnlts fill wi py or oxidized py; at 107.4m GND ctc at 45° TCA						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

PAGE 4 of 6

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B380225	56.39	57.91	**0.158**			VA05052040	1.52
0																						B380226	57.91	59.94	**0.006**			VA05052040	2.03
0																						B380227	59.94	60.96	**0.006**			VA05052040	1.02
10	1	0.1	1.0	40		0.0							10.0									B380228	60.96	62.48	**0.033**			VA05052040	1.52
10	1	0.1	1.0	40		0.0							10.0									B380229	60.96	62.48	**0.038**	PD/CA		VA05052040	1.52
																						B380230	STANDARD 1A		**0.870**	1A		VA05052040	
2	1	4.0	8.0	40		0.0							10.0									B380231	62.48	64.01	**0.017**			VA05052040	1.53
																						B380232	64.01	65.53	**0.024**			VA05052040	1.52
7	6	0.1	0.7	30		0.0							90.0									B380233	65.53	67.06	**0.062**			VA05052040	1.53
0																						B380234	67.06	67.45	**0.012**			VA05052040	0.39
																						B380235	67.45	68.58	**0.022**			VA05052040	1.13
																						B380236	BLANK		**<0.005**			VA05052040	
3	1	0.4	1.0	45		0.0				5.0			10.0									B380237	68.58	70.10	**0.014**			VA05052040	1.52
1	1	1.0	1.0	87		0.0				10.0			5.0									B380238	70.10	71.33	**0.060**			VA05052040	1.23
3	1	6.0	8.0	80	10	9.0	q/chl	4	1	10.0								10.0				B380239	71.33	72.10	**0.044**			VA05052040	0.77
4	1	10.0	19.0	60	45	10.0	q/chl	4	1				10.0									B380240	72.10	72.65	**<0.005**			VA05052040	0.55
4	1	10.0	17.0	45		10.0	q/chl	4	1				10.0									B380241	72.65	73.15	**0.007**			VA05052040	0.50
4	1	10.0	17.0	45		10.0	q/chl	4	1				10.0									B380242	72.65	73.15	**0.008**	DUP		VA05052040	0.50
7	1	3.5	15.0	45		5.0	q	5	1				5.0									B380243	73.15	74.68	**<0.005**			VA05052040	1.53
4	1	4.0	12.0	65		5.0	q	5	1				5.0									B380244	74.68	75.36	**0.008**			VA05052040	0.68
3	6	0.1	0.4	45		0.0				100.0												B380245	75.36	75.76	**<0.005**			VA05052040	0.40
6	1	2.0	3.2	45	80	4.0	q	5	1				10.0									B380246	75.76	76.90	**0.074**			VA05052040	1.14
1	6	0.2	0.2	55						100.0												B380247	76.90	78.42	**<0.005**			VA05054218	1.52
6	1	11.0	19.0	60		6.0	q	5	1														(77.92	78.03)					
8	1	4.0	8.5	60		8.0	q	5	1	20.0			5.0									B380248	78.42	79.25	**0.008**			VA05054218	0.83
8	1	4.0	8.5	60		8.0	q	5	1	20.0			5.0									B380249	78.42	79.25	**0.013**	PD/CA		VA05054218	0.83
																						B380250	STANDARD 6F		**2.860**	6F		VA05054218	
1	1	1.0	1.0	60		0.0							5.0									B380251	79.25	80.77	**0.011**			VA05054218	1.52
2	1	0.5	1.0	60		0.0																B380252	80.77	82.30	**0.016**			VA05054218	1.53
2	4	0.2	0.4	50																		B380253	82.30	83.82	**0.027**			VA05054218	1.52
3	1	1.0	1.5	50						10.0	3.0		3.0				1.0						(82.51	82.76)					
3	6	0.2	0.6	30	10								5.0					70.0				B380254	83.82	85.34	**0.017**			VA05054218	1.52
2	1	0.2	0.4	40		0.0				10.0			10.0									B380255	85.34	86.87	**0.104**			VA05054218	1.53
																						B380256	BLANK		**<0.005**			VA05054218	
3	6	0.2	0.6	20		0.0				100.0								70.0				B380257	86.87	88.39	**0.014**			VA05054218	1.52
1	6	0.2	0.2	40						10.0			80.0					15.0				B380258	88.39	89.92	**0.052**			VA05054218	1.53
2	1	0.2	0.4	45		0.0							0.1									B380259	89.92	91.44	**0.007**			VA05054218	1.52
2	6	0.2	0.4	35		0.0							70.0									B380260	91.44	92.96	**<0.005**			VA05054218	1.52
0																						B380261	92.96	94.49	**0.007**			VA05054218	1.53
																						B380262	92.96	94.49	**0.018**	DUP		VA05054218	1.53
3	6	0.2	0.6			0.0				90.0			10.0					70.0				B380263	94.49	96.01	**0.071**			VA05054218	1.52
0																						B380264	96.01	97.54	**0.153**			VA05054218	1.53
0																						B380265	97.54	99.06	**0.153**			VA05054218	1.52
4	6	0.2	1.0	45		0.0				20.0			60.0					25.0				B380266	99.06	100.58	**0.106**			VA05054218	1.52
4	1	0.1	1.6	60	45	0.0				10.0			10.0		10.0			90.0				B380267	100.58	102.11	**0.058**			VA05054218	1.53
1	4	0.2	0.2	35		0.0																B380268	102.11	103.63	**0.025**			VA05054218	1.52
1	4	0.2	0.2	35		0.0																B380269	102.11	103.63	**0.028**	PD/CA		VA05054218	1.52
																						B380270	STANDARD 6F		**2.850**	6F		VA05054218	
0																						B380271	103.63	105.06	**0.037**			VA05054218	1.43
1	1	5.0	5.0	20		0.0							1.0									B380272	105.06	106.68	**<0.005**			VA05054218	1.62
0																						B380273	106.68	107.40	**0.062**			VA05054218	0.72
2	6	3.0	5.0	55		0.0				30.0			60.0					60.0	40.0			B380274	107.40	108.26	**0.517**			VA05054218	0.86

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 5 of 6	
DRILL HOLE # : DG05-284C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	107.40-114.83	107.40	109.34	Appears to be extremely weathered GND; Difficult to tell due to intense alteration; Core is badly decomposed with very poor recovery; sugary texture; 40% qtz 20% plag 5% Hbl; Bt appears to be absent due to alteration; Alt'd to ser and chl; Qtz veins are broken, remnant massive sulphide vein at 107.96m, 2cm at 55° TCA; Diss py present throughout.		4	3	2		
10		109.34	110.65	GND more competent; Alteration less intense; Disseminated aspy present; Veins contain more sulphides in areas of chloritic alteration		2	2	1		
10		110.65	114.83	QZZ with GND Dyke (?); At 110.65m, 7cm at 80° TCA; Sulphide veins in Dyke, altered by QZZ contains 30% aspy; At 110.80m, 12cm at 80° TCA						
				Euhedral aspy on fracture at 114.26m mnr py also present; 10cm qtz vein at 114.58m; Diss aspy present throughout						
80	114.83-117.17	114.83	117.17	MSED; Black with foliations at 50° TCA; Lineations are crenulated; veins have large selvages; Fractures parallel TCA filled with carb						
70	117.17-123.58	117.17	123.58	QZZ wi interbedded MSED; Foliations at 50°; QZZ host to sulphide veinlets; py and aspy						
80	123.58-134.11	123.58	134.11	MSED; Foliations predom at 45° TCA but locally at 85° at 126.90 to 126.96m and at 128.02 to 128.13m; Boudins and crenulation present						
80	134.11-134.71	134.11	134.71	MSED; Silicified metased and quartzite; no vis ctc; At 134.56m contact with bleached intrusive						
10	134.71-135.72	134.71	135.72	GND med grained bleached intrusive; Alteration makes it difficult to identify less altered section 40% qtz, 20% plag and 15% biot; Likely GND						
80	135.72-138.68	135.72	137.56	MSED; Foliation at 40°; local banding altered to chlorite at 136.82m						
80		137.56	138.68	MSED wi small GND dykes; 8cm at 137.56m at 50° TCA; 4cm at 137.86m at 50° TCA; gouge at 137.96m 20cm at 50° TCA						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

PAGE 6 of 6

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6																			B380275	108.26	109.34	**0.714**		Unable to determine orientation due to decomp.	VA05054218	1.08
																						B380276	BLANK		**0.005**			VA05054218	
1	4	0.2	0.2	45																		B380277	109.34	110.65	**0.250**			VA05054218	1.31
2	1	0.4	0.6	50		2.0	q/chl	4	0													B380278	110.65	111.08	**0.573**			VA05054218	0.43
0																						B380279	111.08	111.98	**0.085**			VA05054218	0.90
4	1	0.4	0.9	25		0.0				15.0			25.0						60.0			B380280	111.98	113.38	**0.056**			VA05054218	1.40
1	6	0.2	0.2	30		0.0							100.0									B380281	113.38	114.30	**0.053**			VA05054218	0.92
1	6	0.2	0.2	30		0.0							100.0									B380282	113.38	114.30	**0.090**	DUP		VA05054218	0.92
1	1	10.0	10.0	65		0.0							1.0									B380283	114.30	114.83	**0.005**			VA05054218	0.53
1	1	0.2	0.2	70						0.1			0.1									B380284	114.83	115.82	**0.050**			VA05054218	0.99
3	1	1.0	0.17	60		0.0							5.0									B380285	115.82	116.97	**0.005**			VA05054218	1.15
3	1	3.0	4.0	60	35	0.0							20.0						80.0			B380286	116.97	118.36	**0.150**			VA05054218	1.39
2	1	1.0	1.4	40		0.0				15.0			20.0									B380287	118.36	119.88	**0.029**			VA05054218	1.52
0																						B380288	119.88	121.39	**0.045**			VA05054218	1.51
																						B380289	119.88	121.39	**0.038**	PD/CA		VA05054218	1.51
																						B380290	STANDARD 3C		**0.088**	3C		VA05054218	
0																						B380291	121.39	122.91	**0.039**			VA05054218	1.52
0																						B380292	122.91	123.64	**0.006**			VA05054218	0.73
4	1	1.0	2.4	60		0.0				0.1			0.1									B380293	123.64	124.42	**0.016**			VA05054218	0.78
1	1	1.0	1.0	60		0.0							1.0						90.0			B380294	124.42	125.94	**0.043**			VA05054218	1.52
1	1	3.0	3.0	60		0.0							0.1									B380295	125.94	126.49	**0.064**			VA05054218	0.55
																						B380296	BLANK		**<0.005**			VA05054218	
1	1	1.0	1.0	30		0.0				5.0			10.0					40.0	10.0			B380297	126.49	128.02	**0.026**			VA05054218	1.53
2	1	2.0	3.0	45		2.0	q/chl	3	1	5.0												B380298	128.02	129.54	**0.017**			VA05054218	1.52
2	6	1.0	1.2	45		0.0							10.0									B380299	129.54	131.06	**0.017**			VA05054218	1.52
1	1	1.0	1.0	45		0.0																B380300	131.06	132.59	**0.005**			VA05054218	1.53
1	4	1.0	1.0	45																		B380301	132.59	134.11	**0.006**			VA05053956	1.52
1	4	1.0	1.0	45																		B380302	132.59	134.11	**0.011**	DUP		VA05053956	1.52
2	6	0.2	0.4	45		0.0				25.0												B380303	134.11	134.71	**0.032**			VA05053956	0.60
2	6	0.2	0.4	45		0.0				10.0								80.0				B380304	134.71	135.68	**0.113**			VA05053956	0.97
1	1	2.0	2.0	40		0.0																B380305	135.68	137.56	**0.010**			VA05053956	1.88
1	1	2.0	2.0	60		5.0	chl	4	1				10.0									B380306	137.56	138.68	**0.009**			VA05053956	1.12
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-285C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:	1028m
BEARING: 000	DIP: -50°
COORD SYSTEM: NAD 27:	EASTING: 459753 NORTHING: 7099042
COORD SYSTEM: NAD 83:	EASTING: 459633 NORTHING: 7099227
NAD 27 (CORRECTED for historic grid):	EASTING: 459723 NORTHING: 7099052
SECTION LINE 459725 (historic grid)	

DATE STARTED: 16-Jun-05 DATE COMPLETED: 19-Jun-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 14.02m
Deviation:
Casing: 14.02m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A

Notes: No plug necessary. Drill oriented by K. Whitehead. EOH corrected by DH (Nov).

FROM	TO	LITHOLOGY
14.02	36.58	MSED
36.58	192.02	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B292215 - B292378

Requisition #: MASP448STRGOL.05Q Date Shipped: 21-Jun-05

Lab Record #: VA05052412 Date Received: 29-Jun-05

Duplicates:	292222; 292242; 292262; 292282; 292302; 292322; 292342; 292362
Preparation Duplicate/ Check Assay:	292229; 292249; 292269; 292289; 292309; 292329; 292349; 292369
Standards:	292230 (5E); 292250 (2B); 292270 (6F); 292290 (7G); 292310 (6F); 292330 (1A); 292350 (5E); 292370 (4D)
Blanks:	292216; 292236; 292256; 292276; 292296; 292316; 292336; 292356; 292376

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	337.9	-51	3.9	4.9
150	336.6	-52.6	2.6	3.6
192.02	338.8	-52.8	4.8	5.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 1 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-14.02	0.00	14.02	Casing (No Recovery)						
80	14.02-36.58	14.02	18.29	MSED; Appearance is black with finely laminated layering (meta-beds), distinguished by minor compositional variation; Complex structure, bedding is from 0 to 60° to CA; qtz veins are parallel to bedding AND convoluted in shape and girth; Cross cutting bedding; very minor limonite.	1				1	
80		18.29	21.34	Veins <1cm through MSED; variable orientations throughout; weakens rock. Gouge section abuts competent (but crumbly) rock at 30° to CA; Gouge length is 20 cm. Bigger veins from 19.81m to 20.34m appear rearranged (see diag in written log); ox'd py concentrated in lenses at margins.	2			1	2	
80		21.34	22.86	Gouge - brecciated MSED, limonite more pervasive where core is broken	2		1	2	2	
80		22.86	24.38	Veins <1cm following bedding plane (30° to CA); offshoots from these veins at 60° to vein itself.	1			1	1	
80		24.38	28.96	Qtz veins (milky) every 10 cm or less, and are parallel to bedding, but a few (~5%) are narrow and 130° to CA (Bedding at 45 deg), Sulphides concentrated at margins of quartz, evidence of motion across veins.	1			1	1	
80		28.96	30.48	Limonite staining on irregular fracture faces is bright orange; Quartz-rich section toward bottom of sample, heavy carbonate alteration creates crumbly white clay to sand texture in 10 cm section at 20° to CA.	1			1	2	
80		30.48	36.58	Silicified MSED; Quartz-rich from large and numerous veins - 90% parallel to metased bedding	1			1	1	
10	36.58 - 192.02	36.58	41.15	GND; contact not seen as recovery is poor and core is v broken up. Lim stained on numerous microfracts and throughout matrix of GND; color is orange-brown with GND texture showing through. White calcite on fracture faces; to 41.15m very broken core, with ave size 2.5cm in diameter.	3			1	2	
10		41.15	43.80	More competent; Regular fractures at 50° and 110° to CA; Avg size 8cm long; limonite still pervasive.	3			1	2	
10		43.80	47.24	Very broken core; Limonite pervasive with calcite on fracture faces; Crumbly clay to sandy texture. From 45.52 to 45.65m carbonate is pervasive (white crumbly texture).	4			1	2	
10		47.24	50.29	V. poor recovery (21-25%), crumbly, carb and lim sand with remnant GND, qtz eyes, and GND pieces, largest 3cm.						
10		50.29	51.82	More competent GND with texture; Limonite near pervasive; so occasional pale orange brown color permeates	2			1	1	
10		51.82	53.34	Similar to above but with quartz veins/sulphide veins						
10		53.34	54.86	GND very broken up with limonite precipitated on fractures (and micro-fracts); Most have calcite crystallization as well, up to 2mm thick on larger faces.	2	1	1	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.5	1.0			0.0				3.0								4.0				B292215	14.02	15.24	<0.005			VA05052412	1.22
																						B292216	BLANK		<0.005			VA05052412	
1	1	4.0	4.0	50																		B292217	15.24	16.76	<0.005		Veins combine sulphide conc in carb/qtz vein.	VA05052412	1.52
1	3	1.5	1.5	5		1.0	q/cb	2	1	10.0			12.0					3.0	3.0										
6	3	3.0	8.0	40		1.0	q/cb	2		5.0								5.0				B292218	16.76	18.29	<0.005			VA05052412	1.53
							s	1																					
0																						B292219	18.29	19.51	<0.005			VA05052412	1.22
3	1	2.0	4.0	30		2.0				8.0								4.0				B292220	19.51	20.34	<0.005		Selvage includes banded layers around qtz and conc of ox-py.	VA05052412	0.83
0																						B292221	20.34	21.34	<0.005			VA05052412	1.00
0																						B292222	20.34	21.34	<0.005	DUP		VA05052412	1.00
4	1	1.0	4.0	80		0.0				8.0								4.0				B292223	21.34	22.86	<0.005		Some pieces	VA05052412	1.52
0																						B292224	22.86	24.38	<0.005			VA05052412	1.52
4	1	2.0	8.0	50		0.0				10.0								5.0				B292225	24.38	25.91	<0.005			VA05052412	1.53
7	1	5.0	13.0	55		3.0	q	2		10.0								5.0				B292226	25.91	27.43	<0.005			VA05052412	1.52
8	1	6.0	24.0	50		10.0	q	2		12.0								5.0				B292227	27.43	28.96	<0.005		mechanical alt'n (breakage) = 3	VA05052412	1.53
6	1	12.0	18.0	60		10.0	q	2		15.0								5.0				B292228	28.96	30.48	<0.005		m=3	VA05052412	1.52
6	1	12.0	18.0	60		10.0	q	2		15.0								5.0				B292229	28.96	30.48	<0.005	PD/CA		VA05052412	1.52
																						B292230	STANDARD 5E		1.405	5E		VA05052412	
3	1	5.0	7.0	50		2.0	q	4	1	10.0								5.0				B292231	30.48	32.00	0.005			VA05052412	1.52
9	1	6.0	15.0	55	30		q	4		1.0								5.0				B292232	32.00	33.53	<0.005			VA05052412	1.53
20	1	6.0	80.0	90	60	0.0				20.0								5.0				B292233	33.53	35.05	<0.005			VA05052412	1.52
4	1	2.0	8.0	50		0.0				5.0								5.0				B292234	35.05	36.58	0.008			VA05052412	1.53
0																						B292235	36.58	38.10	0.05			VA05052412	1.52
																						B292236	BLANK		<0.005			VA05052412	
0																						B292237	38.10	39.62	0.047			VA05052412	1.52
8	1	1.0	8.0	55	45	3.0	q	5	2	2.0			2.0					4.0	0.0			B292238	39.62	41.15	0.173			VA05052412	1.53
4	1	1.5	4.5	45		3.0	q	3	2	2.0	1.0		20.0					5.0	0.0			B292239	41.15	42.67	0.159			VA05052412	1.52
0																						B292240	42.67	44.20	0.083			VA05052412	1.53
5	1	2.0	6.0	35		1.0	q	3	1	0.1									0.0			B292241	44.20	45.72	0.017			VA05052412	1.52
5	1	2.0	6.0	35		1.0	q	3	1	0.1									0.0			B292242	44.20	45.72	0.016	DUP		VA05052412	1.52
0																						B292243	45.72	47.24	0.035			VA05052412	1.52
0																						B292244	47.24	48.77	0.018			VA05052412	1.53
0																						B292245	48.77	50.29	0.108			VA05052412	1.52
0																						B292246	50.29	51.82	0.042			VA05052412	1.53
2	6	0.3	0.3	70	150	1.0	q	3	2	40.0			60.0					4.0	1.0										
1	1	0.5	0.5	25		5.0	q	2	2	1.0								5.0											
							chl	1																					
1	1	4.0	4.0	0		0.0				0.0												B292247	51.82	53.34	0.058			VA05052412	1.52
2	1	2.0	3.0	50			q	2	2	3.0								5.0				B292248	53.34	54.86	0.11			VA05052412	1.52
							s/chl/cb	1																					

DRILL LOG LEGEND - P1	DATE: 16-19-Jun-05	PAGE 3 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		54.86	56.39	Microfractures/veins at 2 angles: 30° and 150° to CA						
10		56.39	57.91	Alt'd GND continues						
10		57.91	59.44	Xenolith (amphibolite, f-grained) 3cm by 3cm at 58.20m.						
10		59.44	60.96	95% loss of core (5% rec); Crumbly with one calcite vein; Chlorite alteration on fracture faces						
10		60.96	64.01	Alt'd GND continues	2	1	1	1	2	
10		64.01	65.53	More altered GND due to increased shear action (mechanical alteration); Qtz eyes in carb-lim rich weakened but competent core.	2	1	1	1	2	
10		65.53	67.07	Veinlets continue to indicate mechanical action and shear for 1st metre; Followed by silicified section (hard - nail won't scratch it, GND texture faded). Sphalerite seen; opaque black; tabular, hard						
10		67.07	68.58	Very broken core with poor recovery (47%)	4	1	1	1	2	
10		68.58	70.10	Strong limonization of GND wi limonitic quartz veins with sphalerite and minor aspy; one unaltered section from 68.9 to 69.2m (between veinlets)	3	1	1	1	2	
10		70.10	73.15	Small areas of unaltered GND; Max 15cm long between fractures and microveinlets of limonite and calcite (to 79.25m)	2	1	1		2	
10		73.15	79.25	Sericite slickenslides are seen on regular fractures at 40° to CA; Sphalerite appears as 2-3mm (max) angular black mineral in middle of vein, associated with cpy and aspy (attached to diff grains of sph); Aspy also disseminated in selvage of veins.	2	1	1		2	
				1cm massive aspy vein at 76.54m; aspy (90%) with calcite (10%); Slickensides still at 76.61m; dendritic growth of biotite on surface overtop of slickenslides						
10		79.25	85.29	Limonized and carbonitized GND; original texture still visible (qtz, bt, etc); but matrix highly carb-rich (yellowish-white) and oxidized powdery limonite (orangey-brown) infiltrates the rock with >1cm selvages.	2	1	1		2	
10		85.29	85.67	Light grey unaltered GND with one qtz-carb vein at low angle	1				1	
10		85.67	86.95	Limonite + carbonate alteration pervasive; Weak, crumbly rock; coarse sand makes up 40% of sample; Max size: 10cm lengths. Color: deep greenish brown with yellowish white patches in coherent pieces	4	2	1	1	3	
10		86.95	88.39	Highly altered to extremely altered. SHEAR ZONE (mechanical alt'n a factor). Quartz eyes visible btwn dark brown-black fine laminations with movement indicators; Sericite slickenslides well developed on planes at 55° to CA; Shear foliation at 80-85° to CA; Gouge clay last 12cm of sample	4	1	1	1	2	
10		88.39	92.96	Crumbly soft rock to sand-size fragmented GND; 90% stained by limonite and carbonate; Colour is med brown; Weak slickensides pronounced in minor sericite, parallel to long axis of fracture face at 55° to CA.	3	1	1	1	2	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	2.0	3.0	50			q	2	2	3.0								5.0				B292249	53.34	54.86	0.107	PD/CA		VA05052412	1.52
							s/chl/cb	1																				
																						B292250	STANDARD 2B		3.04	2B		VA05052412	
0																						B292251	54.86	56.39	0.033			VA05052412	1.53
3	1	2.0	4.0	10		1.0	q	3	0	0.0												B292252	56.39	57.91	0.057			VA05052412	1.52
1	1	0.5	0.5	10		1.0	q	4	1				1.0									B292253	57.91	59.44	0.142			VA05052412	1.53
1	4	0.5	0.5				cb	3	2	0.0												B292254	59.44	60.96	0.168		Carbon broken piece	VA05052412	1.52
3	1	1.5	4.0	30	50	0.5	q	1	2	5.0	1.0							5.0				B292255	60.96	62.48	0.046			VA05052412	1.52
																						B292256	BLANK		<0.005			VA05052412	
2	1	1.0	2.0	50		0.5	q	1	2	1.0								5.0				B292257	62.48	64.01	0.062			VA05052412	1.53
																						B292258	64.01	65.53	0.086			VA05052412	1.52
2	1	0.5	1.0	25	30	1.0	q/chl	1	2						10.0							B292259	65.53	67.07	0.11			VA05052412	1.54
1	1	1.0	1.0	20		1.0	q	2	1													B292260	67.07	68.58	0.121			VA05052412	1.51
							cb	1																				
3	1	1.0	3.0	25		4.0	q	2	3				1.0		5.0				3.0			B292261	68.58	70.10	0.268			VA05052412	1.52
							cb/chl	1																				
3	1	1.0	3.0	25		4.0	q	2	3				1.0		5.0				3.0			B292262	68.58	70.10	0.125	DUP		VA05052412	1.52
							cb/chl	1																				
3	1	4.0	8.0	45		2.0	q	3	2				1.0									B292263	70.10	71.63	0.11			VA05052412	1.53
							chl	1																				
2	1	1.0	2.0	35		1.5	q	3	2		4.0							2.0				B292264	71.63	73.15	0.02			VA05052412	1.52
							chl	1																				
3	1	1.0	2.0	25		3.0	q	3	1			1.0	2.0		8.0							B292265	73.15	74.68	0.151			VA05052412	1.53
							s/chl	1																				
1	1	1.0	1.0	25		6.0	q	3					3.0		2.0							B292266	74.68	76.20	0.029			VA05052412	1.52
							chl	4																				
							cb	2																				
1	6	1.0	1.0	40		0.0			1				90.0					1.0				B292267	76.20	77.72	0.06		1 cm massive aspy vn	VA05052412	1.52
1	1	1.0	1.0	25		6.0	chl	4																				
							q/cb	2																				
1	4	1.0	1.0	45							30.0							5.0				B292268	77.72	79.25	0.034			VA05052412	1.53
1	1	1.0	1.0	25							5.0																	
1	4	1.0	1.0	45							30.0							5.0				B292269	77.72	79.25	0.035	PD/CA		VA05052412	1.53
1	1	1.0	1.0	25							5.0																	
																						B292270	STANDARD 6F		2.81	6F		VA05052412	
0																						B292271	79.25	80.77	0.035			VA05052412	1.52
1	1	2.0	2.0	30		8.0	q	2			10.0		1.0					4.0				B292272	80.77	82.30	0.088			VA05052412	1.53
							chl	3																				
0																						B292273	82.30	83.82	0.016			VA05052412	1.52
2	1	3.0	5.0	40		5.0	q	2	1	5.0	2.0							5.0				B292274	83.82	85.29	0.053			VA05052412	1.47
							chl	1																				
1	3	1.0	1.0	8		0.0				8.0	1.0							5.0				B292275	85.29	85.67	0.116			VA05052412	0.38
																						B292276	BLANK		<0.005			VA05052412	
0																						B292277	85.67	86.95	0.096			VA05052412	1.28
1	3	2.0	2.0	50		0.0				0.1								5.0				B292278	86.95	88.39	0.085			VA05052412	1.44
1	1	1.0	1.0	10		3.0	chl	2	1	0.0												B292279	88.39	89.92	<0.005			VA05052412	1.53

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 5 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		92.96	93.61	Light brown clay dominates this sample (70%) plus quartz eyes and a few <3cm GND (highly altered) chunks.	3	1		3	1	
10		93.61	96.62	Carbonate and limonite altered GND; Pervasive through veinlets and matrix; Crumbly and very broken up.	3	1		1	2	
10		96.62	96.82	Aphanitic; GND texture erased to dark grey/dark green; chloritic and oxidized (sulphides?) and limonite pervasive	4	2	3		2	
10		96.82	99.95	GND s at 93.61-96.63m above, with slightly more sericite	3	2		1	2	
10		99.95	101.13	Highly altered GND. Calcite throughout veinlets and forming large areas. 100% clay to gravelly texture.	4	3	1	2	3	
10		101.13	109.30	Limonite and carbonate altered GND (crumbly and weak core); lim/carb pervasive through veinlets and matrix. Overall colour is whitish brown. Regular low-angle limonite-covered fractures (20°); Weak slickenslides at 108.7m in sericite/chlorite on face @30° to CA.	3	2	1	1	2	
10		109.30	110.65	Zone of extreme alteration surrounding a 2cm calcite vein with alteration to clay in 20cm selvage; Surrounding clay is very altered but competent core; GND texture totally erased to dark green-blue grey, with a matte lustre for 20cm beyond either edge of clay; Extreme edges are yellowish brown from pervasive limonite and calcite throughout core.	3	3	1	2	3	
10		110.65	111.80	GND texture returns, but is infused with limonite and calcite; crumbly texture around	2	1	1	1	2	
10		111.80	114.87	Unaltered GND separated by qtz veins and their selvages; Also microfractures infilled with limonite with tiny (0.5cm) selvages, brown and oxidized; Occurrence ~5 per 20cm (minimum); Weak slickensides on fracture face in calcite/limonite at 30° to CA; Slicks at 30° to CA.	1		1		1	
10		114.87	117.60	Section is very altered; Dark blue-green grey with 1cm-5cm limonized selvages around microfractres; Dull appearance; GND texture erased; Competent core; 100% recovery here.	3	3	2	0	2	
10		117.60	122.65	Unaltered GND except selvages around qtz veins and limonite-covered microfractures; Low angle microfracture faces show slickenslides in chlorite, limonite.	1		1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B292280	89.92	91.44	0.022			VA05052412	1.52
0																						B292281	91.44	92.96	0.018			VA05052412	1.52
0																						B292282	91.44	92.96	0.023	DUP		VA05052412	1.52
0																						B292283	92.96	93.61	0.042			VA05052412	0.65
0																						B292284	93.61	94.49	0.126			VA05052412	0.88
4	1	1.5	4.0	30	60	4.0	q	3	2	5.0					5.0			5.0				B292285	94.49	95.59	0.043		Sulphides in high angle vein	VA05052412	1.10
1	1	1.0	1.0	50		2.0	q	1	2	1.0								5.0				B292286	95.59	96.62	0.115			VA05052412	1.03
							cb	2																					
0																						B292287	96.62	96.82	0.015			VA05052412	0.20
0																						B292288	96.82	97.54	0.04			VA05052412	0.72
0																						B292289	96.82	97.54	0.034	PD/CA		VA05052412	0.72
																						B292290	STANDARD 7G		4.61	7G		VA05052412	
2	1	1.5	3.0	60	50	1.0	q	1	3	2.0			1.0		2.0			5.0	2.0			B292291	97.54	99.06	0.042			VA05052412	1.52
							s	2																					
1	3	1.5	1.5	60		0.5	cb/q	1	2	5.0								5.0				B292292	99.06	99.95	0.036			VA05052412	0.89
1	6	0.8	0.8	60		6.0	cb	4	4				100.0					5.0				B292293	99.95	100.58	0.278			VA05052412	0.63
0																						B292294	100.58	101.13	0.068			VA05052412	0.55
1	1	1.0	1.0	40		2.0	chl/q	2	2	1.0								5.0				B292295	101.13	102.11	0.025			VA05052412	0.98
																						B292296	BLANK		<0.005			VA05052412	
2	3	1.5	2.5	40		10.0	chl/q	2	4						2.0			5.0				B292297	102.11	103.63	0.034			VA05052412	1.52
5	3	1.5	6.0	40		4.0	q/chl	2	2	0.0												B292298	103.63	105.16	0.023			VA05052412	1.53
0																						B292299	105.16	106.68	0.029			VA05052412	1.52
2	3	1.0	2.0	35		6.0	q	1	1				15.0						2.0			B292300	106.68	108.00	0.074			VA05052412	1.32
							cb	3																					
2	1	1.2	2.4	35	50	2.0	q	2	1	3.0			2.0					4.0	2.0			B292301	108.00	109.30	0.105			VA05052412	1.30
2	1	1.2	2.4	35	50	2.0	q	2	1	3.0			2.0					4.0	2.0			B292302	108.00	109.30	0.104	DUP		VA05052412	1.30
1	4	1.5	1.5	20		135.0	cb/s	3	4													B292303	109.30	110.65	0.086			VA05052412	1.35
							chl	1																					
1	1	3.0	3.0			40.0	cb	3	4	2.0								4.0				B292304	110.65	111.80	0.022		Grey qtz	VA05052412	1.15
							q	2																					
							chl	1																					
5	1	4.0	12.0			3.0	q/cb	2	2	3.0					5.0			4.0				B292305	111.80	112.78	0.036			VA05052412	0.98
1	1	4.0	4.0	10		0.0							1.0					3.0				B292306	112.78	113.40	0.026			VA05052412	0.62
2	1	2.0	4.0	60		1.0	q	3	2			1.0	6.0		3.0			2.0	4.0			B292307	113.40	114.87	0.267			VA05052412	1.47
							cb	1																					
3	3	0.5	1.5	30		3.0	q/cb	3	1			1.0	5.0		3.0			1.0	1.0										
2	6	0.5	1.0	30		2.0			3	40.0	0.1		40.0				20.0					B292308	114.87	116.41	0.118		other is hematite	VA05052412	1.54
2	6	0.5	1.0	30		2.0			3	40.0	0.1		40.0				20.0					B292309	114.87	116.41	0.115	PD/CA	other is hematite	VA05052412	1.54
																						B292310	STANDARD 6F		2.8	6F		VA05052412	
2	1	1.5	3.0	50		4.0	q/cb	2	3	15.0								3.0				B292311	116.41	117.60	0.142			VA05052412	1.19
							s/chl	1																					
3	6	1.3	3.5	45		5.0	q/cb	2	3	100.0								3.0											
							s/chl	1																					
3	1	3.0	6.0	35		2.0	q	3	1	2.0	8.0	0.1	2.0					2.0				B292312	117.60	118.87	1.52			VA05052412	1.27
							chl	1																					
2	4	0.4	0.8	25		4.0	q/chl	2	2	0.0												B292313	118.87	120.40	0.277			VA05052412	1.53
2	1	2.5	4.5	25		8.0	q	1	3	5.0					7.0			4.0											

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 1 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		122.65	126.77	Minor altered GND; Veinlets of limonite and calcite pervasive; Max length of unaltered GND is 20cm; Weak slickenslides on low angle (10° to CA) fracture faces	2			1	2	
10		126.77	133.40	Very minor altered GND; Straight grey quartz veins with small selvages (@30-40°) are intersected by one quartz/carb vein with dramatic selvage (irregular and carb-rich); both sets contain po. At intersections po concentrated, up to 50%	1				1	
10		133.40	136.38	Unaltered GND except wide selvages around qtz veins; Very minor limonite on microfractures	1	1	1		1	
10		136.38	150.88	Unaltered GND except narrow selvages adjacent to qtz and qtz-carb veins; Very minor limonite on microfractures; Calcite concentrated on microfractures as well, up to 0.2cm; At 144.42m, wispy veins of calcite and ox'd py extend through unaltered GND; Angle to CA is 20°	1	1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

PAGE 6 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																		Interval						
						Selvages				Sulphides									Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	2																					
3	1	1.5	3.5	70		2.0	q	4	0				1.0		10.0			3.0	2.0			B292314	120.40	121.92	0.29		sph max 10%, min 1%	VA05052412	1.52
							cb	2																					
1	1	1.0	1.0	25		0.5	cb/chl	2	1						3.0			1.0				B292315	121.92	122.65	0.019			VA05052412	0.73
							q	1																					
1	3	1.5	1.5	30		1.0	q/chl	1	1		2.0		8.0					0.0	0.0										
							cb	2																					
																						B292316	BLANK		<0.005			VA05052412	
1	1	3.0	3.0	45		3.0	q/cb	2	2						2.0			2.0				B292317	122.65	123.44	0.181			VA05052412	0.79
1	1	1.0	1.0	30		2.0	q	3	0						1.0			4.0				B292318	123.44	124.97	0.044			VA05052412	1.53
1	4	0.5	0.5	10		2.0	cb	2	4	0.0																			
1	6	0.6	0.6	35		4.0	s	2	1	40.0								3.0				B292319	124.97	125.44	0.077			VA05052412	0.47
							cb	4																					
2	1	1.5	3.0	35		0.5	q	3	3		3.0		5.0					3.0	1.0			B292320	125.44	126.77	0.026			VA05052412	1.33
3	1	1.0	2.0	40	30	2.0	q/cb	3	0		10.0							1.0				B292321	126.77	128.02	0.029			VA05052412	1.25
1	3	0.5	0.5	150		4.0	q	2	1	5.0	5.0							3.0											
							cb	5																					
1	3	0.5	0.5	150		4.0	q	2	1	5.0	5.0							3.0				B292322	126.77	128.02	<0.005	DUP		VA05052412	1.25
							cb	5																					
3	1	2.0	9.0	25		2.0	q	1	1	0.0												B292323	128.02	129.54	0.021			VA05052412	1.52
							cb	3																					
4	1	2.0	6.0	45	30	2.0	q/chl	2			8.0							5.0				B292324	129.54	131.86	0.04			VA05052412	2.32
3	1	1.5	4.5	50		4.0	q	3	1	2.0	2.0							5.0				B292325	131.86	132.59	0.063			VA05052412	0.73
1	6	1.5	1.5	50		10.0	q/chl	3	1	100.0								4.0											
0																						B292326	132.59	133.40	0.053			VA05052412	0.81
4	1	3.0	7.0	25		20.0	q/s/cb	2	1	5.0	2.0							2.0				B292327	133.40	134.46	0.095			VA05052412	1.06
							chl	1																					
1	1	2.0	2.0	45		1.0	q/s/cb	2	0				2.0						1.0			B292328	134.46	135.64	0.043			VA05052412	1.18
							chl	1																					
1	1	2.0	2.0	45		1.0	q/chl	2	0				2.0						1.0			B292329	134.46	135.64	0.055	PD/CA		VA05052412	1.18
							chl	1																					
																						B292330	STANDARD 1A		0.872	1A		VA05052412	
3	1	1.0	3.0	40		0.0							2.0						1.0			B292331	135.64	136.38	0.06			VA05052412	0.74
1	3	1.5	1.5	45		2.0	q	3	0	3.0								2.0				B292332	136.38	137.16	0.031			VA05052412	0.78
							s	2																					
1	1	1.0	1.0	45		0.0				2.0								5.0				B292333	137.16	138.68	0.689			VA05052412	1.52
1	3	1.0	1.0	45		6.0	q/cb/s	1	0	5.0			5.0					4.0											
							chl	4																					
3	1	1.0	3.0	45		2.0	q/cb	2	0				2.0					5.0				B292334	138.68	140.21	0.121			VA05052412	1.53
2	3	0.5	1.0	50		6.0	q/cb	3	0	3.0	3.0							4.0				B292335	140.21	141.73	0.067			VA05052412	1.52
							chl	4																					
							s	2																					
1	1	1.0	1.0	20		4.0	q	4			5.0																		
							s	1																					
																						B292336	BLANK		<0.005			VA05052412	
4	1	0.5	2.0	40		1.0	q	4	0		4.0							1.0				B292337	141.73	143.26	0.409			VA05052412	1.53
							s	1																					
1	1	0.5	0.5	35		0.0				8.0								5.0				B292338	143.26	144.78	<0.005			VA05052412	1.52
2	1	1.0	2.0	35		1.0	q	3			5.0		1.0					2.0	1.0			B292339	144.78	146.30	0.012			VA05052412	1.52
							s	2																					
2	4	0.4	0.8	30		1.0	q	3					5.0						3.0										
							cb/s	2																					

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 9 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		150.88	163.07	Unaltered GND with fewer number of qtz vns and smaller selvages		1	1		1	
10		163.07	170.69	Unaltered GND. Calcite slightly more prevalent; So core not as competent; Calcite up to 0.2cm thick on broken faces		1			1	
10		170.69	178.31			2	1		1	
10		178.31	179.12	Chloritized zone for 65cm; GND texture erased; One small qtz vein seen in centre; Py totally oxidized in clay seams.	1	1	3	1	1	
10		179.12	192.02	Unaltered GND with quartz veins to EOH		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max. (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	1																					
2	1	1.0	2.0	40		1.0	q	2			15.0											B292340	146.30	147.83	0.07			VA05052412	1.53
							chl	1																					
2	3	0.5	1.0	30		3.0	q	2		5.0	1.0							1.0											
							cb	4																					
6	1	1.5	45.0	50		12.0	q/chl	2	0		10.0							1.0				B292341	147.83	149.35	0.224			VA05052412	1.52
							cb	4																					
							s	1																					
6	1	1.5	45.0	50		12.0	q/chl	2	0		10.0							1.0				B292342	147.83	149.35	0.077	DUP		VA05052412	1.52
							cb	4																					
							s	1																					
2	1	1.5	2.0	40		8.0	q/chl	2	0		8.0							0.0				B292343	149.35	150.88	0.014			VA05052412	1.53
							cb	4																					
							s	1																					
7	1	2.0	6.0	25	40	1.0	q	2			10.0		0.1									B292344	150.88	152.40	0.048			VA05052412	1.52
1	1	8.0	8.0	35		1.0	q	3		2.0								5.0											
2	1	6.0	10.0	10		2.0	q	3	0	4.0			1.0		2.0			2.0	2.0			B292345	152.40	153.92	0.037			VA05052412	1.52
3	1	8.0	10.0	35	70	2.0	q	3	0		10.0							1.0				B292346	153.92	155.45	0.209			VA05052412	1.53
2	1	1.0	2.0	30		4.0	q/cb	2					2.0									B292347	155.45	156.97	0.026			VA05052412	1.52
							chl	1																					
0																						B292348	156.97	158.50	0.017			VA05052412	1.53
0																						B292349	156.97	158.50	0.029	PD/CA		VA05052412	1.53
																						B292350	STANDARD 5E		1.405	5E		VA05052412	
4	1	1.0	4.0	15	50	1.0	q	3	0		3.0		5.0					0.0	4.0			B292351	158.50	160.02	0.035			VA05052412	1.52
							chl	1																					
3	1	1.5	3.0	35		1.0	q	3	0		7.0							1.0				B292352	160.02	161.54	0.033			VA05052412	1.52
							s/chl/cb	1																					
2	1	1.5	2.5	50		1.0	q	3	0		5.0							1.0				B292353	161.54	163.07	0.071			VA05052412	1.53
							s/chl/cb	1																					
4	1	0.5	1.0	40	30	1.0	q	3	0				10.0									B292354	163.07	164.59	0.242			VA05052412	1.52
							chl	2																					
3	1	1.0	2.0	50	30	1.0	q	3	0		15.0		5.0									B292355	164.59	166.12	0.036			VA05052412	1.53
							chl	2																					
																						B292356	BLANK		<0.005			VA05052412	
1	3	4.0	4.0	40		6.0	q	2	0		3.0	1.0						2.0	4.0			B292357	166.12	167.64	1.445			VA05052412	1.52
							chl	4																					
3	1	0.5	1.5	30	35	1.0	q	3	0		5.0							5.0				B292358	167.64	169.16	0.084			VA05052412	1.52
1	1	1.0	1.0	30		2.0	q/cb	2	0	2.0	2.0							5.0				B292359	169.16	170.69	0.022			VA05052412	1.53
							chl	1																					
4	1	1.0	4.0	35		5.0	q/chl/s	2			10.0	1.0										B292360	170.69	172.21	0.023			VA05052412	1.52
							cb	1																					
0																						B292361	172.21	173.74	0.02			VA05052412	1.53
0																						B292362	172.21	173.74	0.018	DUP		VA05052412	1.53
2	1	1.3	2.5	30		1.0	q	3			2.0											B292363	173.74	175.26	0.041		Grey Quartz	VA05052412	1.52
1	1	1.0	1.0	15		4.0	q	2			2.0																		
							chl/cb	1																					
5	1	1.2	4.0	35	15	1.0	q/chl	2			5.0											B292364	175.26	176.78	0.02		Grey Quartz	VA05052412	1.52
							cb	1																					
2	1	0.5	1.0	60	50	2.0	chl	3	1													B292365	176.78	178.31	0.1			VA05052412	1.53
2	1	0.5	1.0	30	60	65.0	chl	3	1	20.0								5.0				B292366	178.31	179.12	0.068			VA05052412	0.81
							s	1																					
2	1	0.5	1.0	50		2.0	q	3		2.0								1.0				B292367	179.12	179.83	0.023			VA05052412	0.71
							chl	2																					
5	1	1.5	5.2	60	30	4.0	q	3			5.0							0.0				B292368	179.83	181.36	0.053			VA05052412	1.53
							cb	1																					

DRILL LOG LEGEND - P1	DATE: 16-19-Jun-05	PAGE 11 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other

DRILL LOG LEGEND P2

Date: June 16-19th, 2005

LOGGED BY: M Stone

PAGE 12 of 12

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides								Oxidation							Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
5	1	1.5	0.2	60	30	4.0	q/cb	3			5.0							0.0				B292369	179.83	181.36	**0.131**	PD/CA		VA05052412	1.53
							cb	1																					
																						B292370	STANDARD 4D		**0.433**	4D		VA05052412	
6	1	1.0	4.0	60	30	1.0	q	3			8.0											B292371	181.36	182.88	**0.192**			VA05052412	1.52
							cb	2																					
							chl	1																					
2	1	0.5	1.0	25		1.0	q	3	0		6.0							1.0				B292372	182.88	184.40	**0.014**			VA05052412	1.52
							s	1																					
7	1	1.0	5.0	40		1.0	q	3	0		5.0							1.0				B292373	184.40	185.93	**0.128**			VA05052412	1.53
							s	1																					
5	1	1.0	4.0	45		1.0	q/s	4	0		3.0		5.0					1.0	4.0			B292374	185.93	187.45	**0.02**			VA05052412	1.52
5	1	1.0	3.0	40		3.0	q	3														B292375	187.45	188.98	**0.065**			VA05052412	1.53
							s/chl/cb	2																					
																						B292376	BLANK		**<0.005**			VA05052412	
4	1	2.0	3.5	50	40	1.5	q	3	0	1.0	6.0	0.1	5.0					0.0	1.0			B292377	188.98	190.50	**0.048**			VA05052412	1.52
							cb	2																					
							chl	1																					
4	1	0.5	2.0	50	40	1.0	q	3	0	3.0	10.0		7.0					1.0	0.0			B292378	190.50	192.02	**0.075**			VA05052412	1.52
							s/chl	1																E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-286C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 894m

BEARING: 000 | DIP: -50°

DATE STARTED: 18-Jun-05 | DATE COMPLETED: 20-Jun-05

LOGGED BY: Terry Croteau & Tom Patchell

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459209 NORTHING: 7099284

COORD SYSTEM: NAD 83: EASTING: 459091 NORTHING: 7099469

NAD 27 (CORRECTED for historic grid): EASTING: 459179 NORTHING: 7099294

SECTION LINE(historic grid): 459179

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 22.86

Deviation:

Casing: 22.86

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
22.86	59.64	GND
59.64	70.10	MSED (QZZ)
70.10	75.38	GND
75.38	106.10	MSED with GND Dykes
106.10	149.35	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B380307 - B380385

Requisition #: MASP448STRGOL.05Q Date Shipped: 24-June-05

Lab Record #: VA05053956 Date Received: 5-July-05

Sample Sequence: B380386 - B380442

Requisition #: MASP448STRGOL.05Q Date Shipped: 26-July-05

Lab Record #: VA05055093 Date Received: 7-July-05

Duplicates:	B380322, B380342, B380362, B380382, B380402, B380422, B380442
Preparation Duplicate/ Check Assay:	B380309, B380329, B380349, B380369, B380389, B380409, B380429
Standards:	B380310 (7H), B380330 (4D), B380350 (3C), B380370 (1A), B380390 (4D), B380410 (3C), B380430 (5E)
Blanks:	B380316, B380336, B380356, B380376, B380416, B380436

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
50.0	343.2	-50.5	009.2	010.2
100.0	344.7	-51.0	010.7	011.7
150.0	347.3	-51.3	013.3	014.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE	of 8		
DRILL HOLE # : DG05-286C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-22.86			Casing (No Recovery)						
10	22.86-59.64m			GND (Main Interval). GND is highly altered to sericite/clay making modal composition difficult to interpret. Alteration trends to pervasive lim around 44m. 40% qtz, 20% kspar, 15% bt, 5% hbl.						
10		22.86	27.03	Altered GND, good recovery. Core shows significant alteration to sericite. 2cm massive sulphide veins at 25.12m, 25.18m, 26.13m, 26.48m, 26.52m. At 25.80m, 30cm gouge at 30° to CA terminates at sulphide vein. At 26.21m, 6cm gouge. Dissem py and aspy present to 27.03m.		4		2		
10		27.03	29.17	GND shows less alteration and less sulphides in veins, more competent. Diss aspy.		1		1		
10		29.17	30.48	GND is bleached, altered to ser. Sulphide veins present.		3				
10		30.48	33.63	GND unaltered, except for vein selvages. Core is broken, with decreased recovery as well as sulphide content.		1				
10		33.63	34.60	GND highly altered to clay. Disseminated aspy present. Sometimes concentrated on what appears to be fracture faces.						
10		34.60	34.85	25cm grey qtz vein with fractures filled w/ py; oxidized py on faces.						
10		34.85	44.01	Slightly altered GND w/ diss aspy found throughout. Veins reduce in size, frequency and sulphide content. Core becomes more broken; most gravel-sized at 41.15 to 44.01m. Slickensides present on weathered aspy at 41.65m.	1					
10		44.01	50.29	GND - Start of lim staining on fractures. Core recovery is still poor, core is broken, gravel-sized common. At 44.62m clay gouge, no contact. Aspy present on fractures at veins.	1					
10		50.29	51.82	GND. Limonite staining pervasive throughout sericite altered. Slightly bleached sulphides located on exterior of veins. Mafics removed where veins occur. Carb veinlets invade sporadically.	1	2				
10		51.82	53.34	GND. Slightly altered. Mafics visible. Sericite on fractures. Minor chlorite. Slickensides present on fractures. Qtz veins milky.	1	1				
10		53.34	56.39	Slightly limonized, competent GND. Carb veinlets pervasive. Aspy on fractures slickensided. @54.46m, clay gouge along frac at 80° to CA.	1	1	2	1	1	
10		56.39	57.91	Slightly altered GND, bleached sections with mafics altered to chlorite. @57.02m, GND changes to bleached with py/aspy (0.1-1%). Sulphide veinlets until end of interval.	1	1	3	1	2	
10		57.91	58.93	Slightly altered GND. Cb veinlets, slight lim staining. @57.91m, large quartz vein (4 cm?) with disseminated sulphides (aspy) @58.35m, sheeted qtz vein set (of 3) at 60 ° @58.93m, contact with fault gouge perpendicular to CA.	1		1	1	1	
10		58.93	59.64	Gouge zone, highly altered to clays. Little competency remains. Bleached white, crumbles easily. @59.64m, contact with MSED, no discernable angle		4	2	2		
80	59.64 - 70.10			QZZ metaseds, highly siliceous						
80		59.64	60.96	QZZ, limonized carb veinlets, lamination visible at 50°, 60° and 65° to CA. Clay (ser?) in frac	1			2		
80		60.96	62.48	Limonized QZZ, clay section @ 61.95m	1			1		

DRILL LOG LEGEND P2

8 Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	6												20.0									B380307	22.86	24.38	0.087		too broken for measurements	VA05053956	1.52
2	1	0.5	0.5	75									3.0									B380308	24.38	25.13	0.192			VA05053956	0.75
2	1	0.5	0.5	75									3.0									B380309	24.38	25.13	0.201	PD/CA		VA05053956	0.75
																						B380310	STANDARD 7G		4.420	7G		VA05053956	
1	6	3.0	3.0	75						60.0								90.0				B380311	25.13	25.91	0.240			VA05053956	0.78
4	6	2.0	6.2	30						90.0								15.0				B380312	25.91	27.03	0.187			VA05053956	1.12
2	1	0.5	1.0	40						20.0			10.0									B380313	27.03	28.05	0.138			VA05053956	1.02
4	1	0.2	0.8	60									10.0									B380314	28.05	29.28	0.247			VA05053956	1.23
4	1	0.2	0.8	60									30.0									B380315	29.28	29.80	0.179			VA05053956	0.52
																						B380316	BLANK		<0.005			VA05053956	
5	1	0.2	1.0	60						20.0			10.0									B380317	29.80	30.48	0.276			VA05053956	0.68
1	1	0.5	0.5	60						5.0	3.0		2.0									B380318	30.48	32.00	0.145			VA05053956	1.52
4	1	0.5	1.2	60		5.0	q/chl	4	0				10.0									B380319	32.00	33.53	0.291			VA05053956	1.53
																						B380320	33.53	34.60	0.177			VA05053956	1.07
1	1	25.0	25.0							35.0												B380321	34.60	34.85	1.080			VA05053956	0.25
1	1	25.0	25.0							35.0												B380322	34.60	34.85	0.359	DUP		VA05053956	0.25
4	1	2.0	3.2	50									0.1									B380323	34.85	36.25	0.182			VA05053956	1.40
3	1	1.0	2.2	50		2.0	q/chl	3	0				10.0									B380324	36.25	37.58	0.364			VA05053956	1.33
2	1	0.2	0.4	80									5.0									B380325	37.58	39.08	0.181			VA05053956	1.50
1	1	0.2	0.2	60									0.1									B380326	39.08	40.58	0.132			VA05053956	1.50
4	1	0.2	0.8	60		5.0	q/s	3	0				10.0									B380327	40.58	42.08	0.180			VA05053956	1.50
1	1	0.2	0.2	70		3.0	q	3	0	1.0			3.0									B380328	42.08	43.58	0.165			VA05053956	1.50
1	1	0.2	0.2	70		3.0	q	3	0	1.0			3.0									B380329	42.08	43.58	0.179	PD/CA		VA05053956	1.50
																						B380330	STANDARD 4D		0.425	4D		VA05053956	
1	6	0.2	2.0	60									10.0					90.0				B380331	43.58	44.01	0.213			VA05053956	0.43
1	1	0.2	0.2	80									10.0									B380332	44.01	45.72	0.076			VA05053956	1.71
1	1	0.2	0.2	60									10.0									B380333	45.72	47.24	0.089			VA05053956	1.52
																						B380334	47.24	48.77	0.142			VA05053956	1.53
1	1	2.0	2.0	75		1	q	4	0				0.1									B380335	48.77	50.29	0.144			VA05053956	1.52
																						B380336	BLANK		<0.005			VA05053956	
5	1	2.5	4.5	70	50	5.0	q/cb	4					3.0									B380337	50.29	51.82	0.048			VA05053956	1.53
7	1	1.5	3.5	70		0.25	q	2		0.1								10.0				B380338	51.82	53.34	0.069			VA05053956	1.52
8	1	0.3	1.8	70		0.6				0.1												B380339	53.34	56.39	0.325			VA05053956	3.05
3	1	0.3	1.0	80		0.3	chl	3	2	2.0			2.0					1.0				B380340	56.39	57.02	0.212			VA05053956	0.63
4	6	0.2	0.8	65		0.2	q/chl	2	1	0.1			10.0					1.0	2.0										
2	1	0.2	0.4	50		0.4	chl			3.0								4.0				B380341	57.02	57.91	0.089			VA05053956	0.89
1	3	0.2	0.2	60																									
2	6	0.2	0.4	60		0.2	q/chl	2	1	40.0			60.0					20.0	5.0										
2	6	0.2	0.4	60		0.2	q/chl	2	1	40.0			60.0					20.0	5.0			B380342	57.02	57.91	0.109	DUP		VA05053956	0.89
2	1	0.2	0.4	50		0.4	chl			3.0								4.0											
1	3	0.2	0.2	60																									
8	1	0.4	3.0	60	90	0.3	chl	2	1				5.0					1.0				B380343	57.91	58.93	0.210			VA05053956	1.02
1	1	4.0	4.0	50		1.0	chl						15.0					1.0	5.0										
1	6	0.2	0.2	35		0.2	q	1	1				100									B380344	58.93	59.64	0.116			VA05053956	0.71
																						B380345	59.64	60.96	0.028			VA05053956	1.32
1	6	0.2	0.2	65						95.0			5.0					5.0				B380346	60.96	62.48	0.104			VA05053956	1.52

DRILL LOG LEGEND P1	DATE: June 22-25, 2005	PAGE 3 of 8	
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		62.48	67.06	Slight limonitic colors (orange/brown). Core is broken; laminations visible on some whole pieces 30° to CA. Two small qtz veinlets x-cut bedding but no visible sulphides. Two 2cm qtz veins parallel bedding. In between 64.01-65.53m, qtz pieces show aspy, but no structure can be inferred.						
80		67.06	70.10	QZZ, grey with no lim. In pieces. Large qtz vein chunks visible (w/ trace aspy) but no visible measurement could be made. Section broken to gravel/cobble size. Poor recovery from 68.58 - > 70.10m.	0					
10	70.10-72.16	70.10	72.16	Highly altered GND. Bleached light green/white/off white. Milky qtz veins. Altered to clay. Py veinlet (<.2cm) 35° to CA. Sheeted qtz veins.10cm apart, 0.3cm thick at 50° to CA. @72.16m, contact with MSED at 60° to CA.						
80	72.16 - 72.61	72.16	72.61	MSED highly silicified, bleached whitish grey. Chloritized vein contact at 72.61m at 90° to CA.		1	1	1		
10	72.61 - 75.38	72.61	73.45	Highly clay altered GND. Bleached sericite rich, mafics present		4		2		
10		73.45	74.33	Highly chloritized GND - V. green colour, few mafics present			4		1	
10		74.33	75.38	Highly altered GND. Bleached white/green. No mafics present. Chalky, brittle but competent. Diss aspy found from 75.14 - 75.38m.		4	2	4	1	
80	75.38 - 78.53	75.38	76.20	MSED - Aspy in veinlets, 3 at 50° to CA. Parallel laminations. Highly silicified, clay altered.		2		3	1	
		76.20	78.53	Diss sulphides: 30% py. Parent rock MSED with high silicification. Foliation undulating. Cave in @ 77.72m. Small sulphide veinlets at 40° to CA, py on frac. Carb veinlets throughout.		1		1	1	
10	78.53-85.90	78.53	85.90	Highly altered GND. Bleached white/green, little to no mafics. Bt almost completely altered to chl. Speckled green color. At 82.73 - 83.47m, Small undulation of MSED bottom contact at 45-50° to CA.		1	4	1	1	
80	85.90-89.20	85.90	89.20	MSED: Regular qtz veins along foliation. Black, light grey banding. QZZ to phyllite. Small sections of GND visible (<10 cm typically, not throughout entire circumference of core). Foliation at 45- 65°. Qtz infilled in between foliation.	1	1	1			

DRILL LOG LEGEND P2

8 Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages			% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
									Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5 (0-5)	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	2.0	3.5	30		0.0															B380347	62.48	64.01	0.068			VA05053956	1.53
1	6	0.2	0.2									75.0									B380348	64.01	65.53	0.082			VA05053956	1.52
1	6	0.2	0.2									75.0									B380349	64.01	65.53	0.078	PD/CA		VA05053956	1.52
																					B380350	STANDARD 3C		0.089	3C		VA05053956	
																					B380351	65.53	67.06	0.014			VA05053956	1.53
																					B380352	67.06	68.58	0.015			VA05053956	1.52
									0.1												B380353	68.58	70.10	0.074		Relic quartz pieces	VA05053956	1.52
2	1	0.3	0.5	30	150	0.0			0.1												B380354	70.10	71.63	0.070			VA05053956	1.53
3	1	0.3	0.9	35		0.2	chl	2 1													B380355	71.63	72.16	0.046			VA05053956	0.53
																					B380356	BLANK		<0.005			VA05053956	
0																					B380357	72.16	72.61	0.016			VA05053956	0.45
3	1	0.5	1.0	80	60	3.0	chl	3	0.0												B380358	72.61	73.45	0.037			VA05053956	0.84
3	1	0.4	1.0	75		0.5	chl														B380359	73.45	74.33	0.049			VA05053956	0.88
																					B380360	74.33	75.14	0.028			VA05053956	0.81
1	6	0.2	0.2	70					5.0			95.0									B380361	75.14	75.38	0.006			VA05053956	0.24
1	1	0.2	0.2	70		0.2	chl	2 1																				
1	6	0.2	0.2	70					5.0			95.0									B380362	75.14	75.38	0.012	DUP		VA05053956	0.24
1	1	0.2	0.2	70		0.2	chl	2 1																				
1	1	0.5	0.5	50		0.2	q	1 1													B380363	75.38	76.20	0.012			VA05053956	0.82
2	1	0.3	0.6	60	30	0.2	s	1 1	0.0												B380364	76.20	77.72	0.046			VA05053956	1.52
3	6	0.2	0.6	30					95.0								60.0											
3	1	0.2	0.6	50					10.0			0.1									B380365	77.72	78.53	0.049			VA05053956	0.81
3	1	0.2	0.7	60		0.5	chl	4 2	10.0								80.0				B380366	78.53	78.92	0.038			VA05053956	0.39
							s	2																				
							q	1																				
1	1	0.4	0.4	60		1.0	chl	4				0.1									B380367	78.92	79.25	0.047			VA05053956	0.33
							s	2																				
3	1	1.5	1.5	55	75	0.5	chl	1 2													B380368	79.25	80.77	0.054			VA05053956	1.52
							s	3 1																				
3	1	1.5	1.5	55	75	0.5	chl	1 2													B380369	79.25	80.77	0.054	PD/CA		VA05053956	1.52
							s	3 1																				
																					B380370	STANDARD 1A		0.880	1A		VA05053956	
7	1	1.0	4.5	50		0.5	chl	1 1	5.0		10.0						4.0				B380371	80.77	81.47	0.021		max ⅝'s py + aspy	VA05053956	0.70
1	6	0.6	0.6	65		0.3	q	1 1	90.0																			
1	6	0.2	0.2	50		0.0			50.0								80.0				B380372	81.47	82.30	0.030			VA05053956	0.83
4	1	0.4	1.5	45		1.0	chl	3 1	0.1			0.1																
							s	2																				
1	6	5.0	5.0	80					50.0			35.0					80.0				B380373	82.30	82.73	0.288			VA05053956	0.43
1	1	0.6	0.6	70		0.3	chl	1 1	25.0								90.0				B380374	82.73	83.47	0.026			VA05053956	0.74
6	1	1.2	3.0	55		0.4	chl	3 1	0.1			0.1					20.0				B380375	83.47	84.14	0.151			VA05053956	0.67
1	6	0.2	0.2	50		0.2	q	1 1	80.0			5.0																
																					B380376	BLANK		<0.005			VA05053956	
5	1	4.0	12.0	45	75							0.1									B380377	84.14	85.45	0.034			VA05053956	1.31
1	1	10.0	10.0			0.0			0.1			0.1																
1	1	0.6	0.6	60		0.3	5	3 0				0.1					2.0				B380378	85.45	85.90	0.037			VA05053956	0.45
1	6	0.5	0.5	50		0.0			50.0			10.0					90.0				B380379	85.90	86.87	0.010			VA05053956	0.97
12	1	2.0	13.0	50	110	1.0	chl	3	10.0			0.1					80.0										5-10% py		
1	3	0.2	0.2	20					2.0			0.1																
4	1	0.5	1.8	40	25	0.0			10.0												B380380	86.87	88.39	0.007			VA05053956	1.52
4	1	0.3	1.1	65		0.5	s	2 1													B380381	88.39	89.20	0.021			VA05053956	0.81
1	6	0.2	0.2	65					100.0								90.0											

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE 5 of 8		
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	89.20-90.80	89.20	90.80	Small section of highly altered GND. Olive green colour. Few mafics. Slowly grades into MSED, starting @ 89.97m with xenoliths of MSED in GND. Veining sheeted, often paralleling laminations.	1	2	4	1	1	
80	90.80 - 99.06	90.80	91.54	MSED: Silicified. Some sections showing foliation @ 60° to CA. Sulphide vein at 91.22m.	1	2	1		2	
		91.54	94.90	Black, relatively unsilicified MSED. Planar foliations. Qtz not as infilled as above. Foliations at 30-40° to CA	1	1	1	2		
80		94.90	97.54	Slightly more silicified MSED. Foliations at 50° to CA where visible. Qtz infilled.	1	1		1	1	
		97.54	99.06	Darker MSED. Dark grey to black, some carbonate veinlets. Little silicification. @99.06m - contact w/ GND (fine grained) is @50°.	2	1			1	
11	99.06 -100.85	99.06	100.85	Speckled GND, yellowish tinge, to otherwise dark grey GND. Fine grained.	1	2	2	1		
80	00.85 - 103.4	100.85	103.47	MSED. Altered, silicified. Whitish green w/ abundant qtz infilling. Some weathering to clay w/ qtz eyes	2	2		1	1	
10	03.47 - 106.1	103.47	106.10	Dark grey to black GND. Few crystals visible. Some biotite and amphiboles but very dark colour. Many carb veinlets	2	1	1	1	1	
80	06.10 - 149.3	106.10	106.68	Highly altered MSED. Qtz invasive everywhere. Colour: green/light green w/ abundant carb veinlets	2	3	1	1	2	
80		106.68	108.20	MSED. Milky qtz veinlets spreading out randomly. Foliations @ 50° to CA. Sulphides cross cuts foliation.	3	1	1		1	
80		108.20	115.82	MSED, foliations at 50° alternating bands of light and black. Foliation often infilled with qtz. Broken, weathered section @ 112.20m. Pieces are angular and range from sand to pebble size.	1	1		1	2	
80		115.82	128.02	MSED altered to green color in few locations. @120.40m, S fold visible; perpendicular to core axis with chl band in middle. Many large qtz veins, but little visible mineralization. @119.07m, Cave in rubble; low angle predominant (<20°) carb veinlets. Qtz veins clear @123.44m, large aspy vein @ 126.49 - 127.84m, sulphides located on margins of small qtz veins, cross cutting MSEDS @ 20°-40° to CA opposite 50° MSED.	1	2	1		1	

DRILL LOG LEGEND P2

8 Ox. State

0 = No Alteration 0 = No Oxidized Sulphides

5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	6	0.2	0.2	65						100.0								90.0				B380382	88.39	89.20	0.013	DUP		VA05053956	0.81
4	6	0.2	0.8	40		1.2	s	3	1	40.0								20.0				B380383	89.20	90.80	0.027			VA05053956	1.60
							q	2																					
4	1	1.2	2.0	45		1.0	chl	2	1	2.0			1.0					10.0											
1	6	0.3	0.3	40		0.5	5	4		40.0			60.0					4.0				B380384	90.80	91.54	0.024			VA05053956	0.74
5	1	1.0	2.0	40	130					0.1			0.1					4.0											
3	1	1.0	2.5	50	30					0.1												B380385	91.54	92.96	0.008			VA05053956	1.42
1	6	0.2	0.2	50		0.6	q	4		20.0								4.0											
8	1	1.0	4.2	30	150	0.2	chl	1	1	5.0												B380386	92.96	94.49	0.024			VA05055093	1.53
3	6	0.2	0.6	50		11.0	q	5		20.0			15.0																
																						B380387	94.49	94.90	0.007			VA05055093	0.41
2	1	1.2	1.8	40		0.3	cb	3		0.0												B380388	94.90	96.01	0.007			VA05055093	1.11
2	1	1.2	1.8	40		0.3	cb	3		0.0												B380389	94.90	96.01	0.008	PD/CA		VA05055093	1.11
																						B380390	STANDARD 4D		0.418	4D		VA05055093	
5	1	2.2	7.0	50	150	0.5	q	3		5.0												B380391	96.01	97.54	0.041			VA05055093	1.53
							chl	1																					
3	1	0.8	1.4	60						10.0												B380392	97.54	99.06	0.038			VA05055093	1.52
3	1	3.1	6.8	60	20	0.2	q/chl	1		0.1			0.1					80.0				B380393	99.06	99.91	0.023			VA05055093	0.85
1	1	0.4	0.4	50		1.0	chl	3		1.0								5.0				B380394	99.91	100.85	0.023		Milky white qtz w/ py on margin	VA05055093	0.94
3	1	0.3	0.9	90	110	0.2	chl	1		5.0																			
2	1	3.0	3.9	70						20.0								60.0				B380395	100.85	102.11	0.008			VA05055093	1.26
1	1	0.9	0.9	45		0.2	s	1		25.0								40.0				B380396	102.11	103.47	0.012		Missed Blank; No Stamp	VA05055093	1.36
1	6	0.3	0.3	40		0.0				95.0								90.0											
0																						B380397	103.47	103.88	0.014			VA05055093	0.41
1	6	0.3	0.3	25		0.0				60.0								50.0				B380398	103.88	105.16	0.053			VA05055093	1.28
3	1	0.7	1.5	50	120	1.0	s/chl	2	1	2.0								10.0											
0																						B380399	105.16	106.10	0.075			VA05055093	0.94
3	1	1.0	3.0	50						15.0								10.0				B380400	106.10	106.68	0.029			VA05055093	0.58
1	1	2.5	7.5	65		0.0				0.0												B380401	106.68	108.20	0.018			VA05055093	1.52
1	6	0.2	0.2	40		3.2	q/chl/s	5		99.0			1.0																
1	6	0.2	0.2	40		3.2	q/chl/s	5		99.0			1.0									B380402	106.68	108.20	0.011	DUP		VA05055093	1.52
4	1	1.3	40.0	60	50	0.0				0.0												B380403	108.20	109.73	0.010			VA05055093	1.53
1	6	0.4	0.4	150		0.0				30.0								100.0											
1	1	1.0	1.0	40	0	0.2	s	2		0.0												B380404	109.73	111.25	0.019			VA05055093	1.52
1	6	0.4	0.4	40		0.5	s/chl	4		15.0			5.0					30.0											
1	1									0.0												B380405	111.25	112.78	0.064		Relic vein	VA05055093	1.53
2	1	4.0	6.0	50		0.2	chl	2		0.0												B380406	112.78	114.30	<0.005			VA05055093	1.52
2	1	0.2	0.4	40	25	0.2	chl	1		10.0								20.0				B380407	114.30	115.82	<0.005			VA05055093	1.52
4	1	9.0	18.0	65	50					0.1								30.0				B380408	115.82	117.35	0.007			VA05055093	1.53
4	1	9.0	18.0	65	50					0.1								30.0				B380409	115.82	117.35	0.008	PD/CA		VA05055093	1.53
																						B380410	STANDARD 3C		0.089	3C		VA05055093	
6	1	1.2	70.0	50	130																	B380411	117.35	118.87	<0.006			VA05055093	1.52
2	1	10.0	16.0	70	50	0.5	s/chl	2																					
5	1	3.5	7.0	50	150	0.3	chl	4														B380412	118.87	120.40	0.020			VA05055093	1.53
1	1	5.0	5.0	50		0.0				0.0												B380413	120.40	121.92	0.024			VA05055093	1.52
1	6	0.2	0.2	140						25.0			1.0																
2	6	0.5	0.9	150		0.0				30.0			3.0					15.0				B380414	121.92	123.44	0.017		Crosscuts foliation	VA05055093	1.52
3	1	10.0	21.0	50	150																								
1	6	0.3	0.3	150		1.2	s	4					80.0					40.0				B380415	123.44	123.71	0.039			VA05055093	0.27
																						B380416	BLANK		<0.006			VA05055093	

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE 7 of 8	
DRILL HOLE # : DG05-286C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd **Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		128.02	131.77	Clay gouge at start of interval.MSEDS are much more silicic with qtz invading between foliations and replacing entire sections (up to 15 cm wide). Qtz has green color while seds are dark grey/black. Foliations planar. Fracture planes along foliation still at 50° to CA. Qtz veins crosscut through foliation and infiltrate between. @131.06m - foliation undulating and ends abruptly, with clay and breccia at terminus.	1	1	3	1	2	
80		131.77	134.11	MSED more bleached, white/light grey/yellow tint with green colouration. Trace diss sulphides. Core broken to small cobbles. Qtz veinlets show selvage, often more visible than the veins. Seds are slightly steeper at 60° to CA	1	1			2	
80		134.11	138.20	MSEDS darker, less qtz, though still prevalent in between foliation. MSEDS darkening with depth, becoming speckled and some brown color showing.	2	3		1	1	
80		138.20	142.97	Bleached and highly fractured/weathered MSED. Color light green to white, rich in clay. Foliation barely visible. Foliations at 60-70° to CA @143.26m - Mislatch	2	5	3	2	2	
80		142.97	149.35	Black/white banded MSED. Silica rich with large section of quartz. Green tint hints at chlorite. Veins cross cut MSED. @148.25m, po veinlets very abundant.	1	1	2	1	1	
	EOH									

DRILL LOG LEGEND P2

8 Ox. State

0 = No Alteration 0 = No Oxidized Sulphides

5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
6	1	3.1	7.0	70	130	1.0	chl	5		10.0												B380417	123.71	124.92	0.005			VA05055093	1.21
1	6	0.3	0.3	40		0.0				40.0			2.0					30.0				B380418	124.92	126.49	<0.005			VA05055093	1.57
2	1	0.4	0.6	40	20	0.2	s	1		20.0			0.1					60.0				B380419	126.49	128.02	0.008			VA05055093	1.53
1	1	2.5	2.5	20		0.0				0.0												B380420	128.02	129.54	0.010			VA05055093	1.52
2	1	0.5	0.8	20		0.0				0.0												B380421	129.54	131.06	0.012			VA05055093	1.52
2	1	0.5	0.8	20		0.0				0.0												B380422	129.54	131.06	0.020	DUP		VA05055093	1.52
0																						B380423	131.06	131.77	<0.005			VA05055093	0.71
0																						B380424	131.77	132.59	<0.005			VA05055093	0.82
																						B380425	132.59	134.11	<0.005			VA05055093	1.52
1	1	0.4	0.4	140																		B380426	134.11	135.64	0.009			VA05055093	1.53
1	1	2.5	2.5	20		4.0	s/chl	4		15.0			0.1					50.0				B380427	135.64	137.16	<0.005			VA05055093	1.52
2	1	2.0	3.1	70						5.0												B380428	137.16	138.20	<0.005			VA05055093	1.04
1	6	0.4	0.4	130						20.0																			
1	6	0.4	0.4	130						20.0												B380429	137.16	138.20	<0.005	PD/CA		VA05055093	1.04
																						B380430	STANDARD 5E		1.470	5E		VA05055093	
0																						B380431	138.20	138.68	<0.005			VA05055093	0.48
1	6	0.3	0.3	150		0.0				5.0								95.0				B380432	138.68	140.21	0.010			VA05055093	1.53
3	1	1.2	3.2	55		0.5	chl	4		10.0												B380433	140.21	141.73	0.030			VA05055093	1.52
4	6	0.2	0.8	55	30	0.5	s/chl	2		40.0			20.0																
1	1									0.0												B380434	141.73	142.97	<0.005		Relict vein	VA05055093	1.24
1	6									30.0			5.0														Relict vein		
1	1	0.5	0.5	140		0.3	s	2		5.0												B380435	142.97	143.26	<0.005			VA05055093	0.29
																						B380436	BLANK		<0.005			VA05055093	
0																						B380437	143.26	144.78	<0.005			VA05055093	1.52
3	1	0.9	2.6	30	150	1.0	s/chl	5		0.1			0.1									B380438	144.78	146.20	0.009			VA05055093	1.42
1	1	15.0	15.0	60		5.0	chl	5		0.0												B380439	146.20	147.83	<0.005			VA05055093	1.63
1	1	0.5	0.5	130		0.0				10.0												B380440	147.83	148.44	0.164		Po veinlets	VA05055093	0.61
2	1	0.6	1.1	130		1.2	chl	4		20.0			1.0									B380441	148.44	149.35	0.006			VA05055093	0.91
2	1	0.6	1.1	130		1.2	chl	4		20.0			1.0									B380442	148.44	149.35	<0.005	DUP		VA05055093	0.91
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-287C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 980m

BEARING: 000 | DIP: -50°

DATE STARTED: 19-Jun-05 | DATE COMPLETED: 22-Jun-05

LOGGED BY: Terry Croteau
June 22-25, 2005

CONTRACTOR:
Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459608 NORTHING: 7099195
COORD SYSTEM: NAD 83: EASTING: 459490 NORTHING: 7099383
NAD 27 (CORRECTED for historic grid): EASTING: 459578 NORTHING: 7099205

SECTION LINE(historic grid): 459578

DRILLING DETAILS

Hole Diameter: HQ
Overburden:17.07m
Deviation:
Casing: 17.07m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B292379-B292500
Requisition #: MASP448STRGOL.05Q Date Shipped: June 24, 2005
Lab Record #: VA05053953, VA05055092 Date Received: July 4 & 7, 2005

Sample Sequence: B381601-B381716
Requisition #: MASP448STRGOL.05Q Date Shipped: June 26, 2005
Lab Record #: VA05055279 Date Received: July 8, 2005

Duplicates:	B292382; B292402; B292422; B292442; B292462; B292482; B381602; B381622; B381642; B381662; B381682
Preparation Duplicate/ Check Assay:	B292389; B292409; B292429; B292449; B292469; B292489; B381609; B381629; B381649; B381669
Standards:	B292390 (1A); B292410 (3C); B292430 (5E); B292450 (6F); B292470 (7G); B292490 (2B); B381610 (7G); B381630 (3C); B381650 (4D); B381670 (3C)
Blanks:	B292396; B292416; B292436; B292456; B292476; B292496; B381616; B381636; B381656; B381676

FROM	TO	LITHOLOGY
17.07	219.46	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	339.0	50.2	005.0	006.0
150.0	340.0	48.6	006.0	007.0
219.5	342.0	47.6	008.0	009.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 1 of 10	
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-17.07m	0.00	17.07	Casing (no core recovery).						
10	17.07-219.46m	17.07	19.81	GND is broken w/ lim staining on frac, becoming pervasive @ 21.02m. Pieces are 10cm to gravel-sized, mixed w/ sugary texture. Recovery is poor.	2			1		
10		19.81	21.96	Core is more competent, recovery is good.	1			1		
10		21.96	22.86	Core is reddish colour and has dissem aspy. Contact w/ gouge @ 50° to CA @ 22.50m. Gouge is 7cm in width & contacts w/ limonized GND on other side.	1			1		
10		22.86	24.38	Core becomes more broken, pervasive lim & on frac sfc's. Trends to more clay alteration @ 24.00m.	2			2		
10		24.38	25.30	Core is softer; altered to clay. Sericite becomes dominant clay. Recovery good, still competent.	2	4				
10		25.30	27.43	Core is less competent & broken. Lim is pervasive and on frac. Pieces are gravel-sized, some show rounded faces.	2					
10		27.43	30.11	Core becomes more competent. Lim pervasive and on frac.	2					
10		30.11	31.52	Core is alt'd to clay, sugary texture. Dark red iron staining; possible qtz, py.	2	3		2		
10		31.52	32.00	Less ser alt'n, core is more competent. Good recovery, lim pervasive & frac.	2	2		1		
10		32.00	35.58	More intense ser alt'n, core is more fractured, recovery less. @ 33.47m: 5cm clay gouge @ 45° to CA.	2	3		2		
10		35.58	36.11	Core competent but fractured, lim on frac.	1	0		1		
10		36.11	36.74	Contact @ 45° w/ decomposed GND. Highly alt'd to clay w/ pervasive lim soft, but competent. Qtz eyes and GND frags present. Zone of hydrothermal alt'n.	4	3		3		
10		36.74	38.33	Return to competent GND. Lim on frac, minor pervasives. Vns crosscut frac angle. Vns @ 40°, frac @ 130°.	1			1		
10		38.33	39.62	Alt'd to sugary texture. Qtz eyes and GND frags present.	4	3		3		
10		39.62	47.02	GND becomes competent, less pervasive lim, mostly on fracs. Fracs predominantly @ 30° to CA, as are carb vnlets. 8cm clay gouge @ 44.60m @ 45° to CA, and 4cm clay gouge @ 44.75m @ 45° to CA.						
10		47.02	48.26	gravel size frags, lim pervasive and on frac.	2			2		
10		48.26	51.62	core more competent, recovery increases. fracs @ 40° and 145°. less pervasive lim, lim on fracs.	1			1		
10		51.62	51.82	GND soft w/ sugary texture, qtz eyes and GND frags present. relict qtz vn @ 51.82m. likely hydrothermal alt. lim pervasive.	3					
10		51.82	53.34	recovery decreases, core becomes fragmented, ser alteration increases on fracs. frags are gravel-sized to 15cm and angular.	3	2		1		
10		53.34	54.05	GND is competent, good recovery. pervasive lim & deep red stained. oxidized sulfide vns--red stain may be related to oxpy.	3			1		
10		54.05	60.96	core is more competent w/ less pervasive lim. fracs still show heavy lim stain, fracs have NO preferred orientation.	1					
10		60.96	61.14	moderately alt to chl, qtz vn is fractured and offset. aspy is oxidized heavily and has left vugs.	2	1		1		
10		61.14	67.06	core is becoming more competent, minor pervasive lim, mostly on fracs. few vns, fracs have no preferred orientation.	2	1		1		

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS									% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
																							B292379	17.07	18.29	0.087			VA05053953	1.22
																							B292380	18.29	19.81	0.051			VA05053953	1.52
																							B292381	19.81	21.34	0.013			VA05053953	1.53
																							B292382	19.81	21.34	0.017	DUP		VA05053953	1.53
																							B292383	21.34	21.96	0.007			VA05053953	0.62
																							B292384	21.96	22.86	0.031			VA05053953	0.9
																							B292385	22.86	24.38	0.022			VA05053953	1.52
																							B292386	24.38	25.30	0.150			VA05053953	0.92
																							B292387	25.30	26.60	0.055			VA05053953	1.3
																							B292388	26.60	28.02	0.070			VA05053953	1.42
																							B292389	26.60	28.02	0.090	PD/CA		VA05053953	1.42
																							B292390	STANDARD 1A		0.836	1A		VA05053953	
																							B292391	28.02	29.14	0.045			VA05053953	1.12
																							B292392	29.14	30.11	0.027			VA05053953	0.97
																							B292393	30.11	30.48	0.067			VA05053953	0.37
																							B292394	30.48	31.52	0.068			VA05053953	1.04
																							B292395	31.52	32.00	0.070			VA05053953	0.48
																							B292396	BLANK		<0.005			VA05053953	
																							B292397	32.00	33.53	0.034			VA05053953	1.53
1	1	1.0	1.0	45		0.0																	B292398	33.53	35.05	0.084			VA05053953	1.52
	1	0.2	0.2	25		0.0							5.0										B292399	35.05	36.11	0.015			VA05053953	1.06
																							B292400	36.11	36.74	0.178			VA05053953	0.63
2	1	0.2	0.4	45		0.0							1.0										B292401	36.74	38.10	0.046			VA05053953	1.36
2	1	0.2	0.4	45		0.0							1.0										B292402	36.74	38.10	0.068	DUP		VA05053953	1.36
																							B292403	38.10	39.62	0.019			VA05053953	1.52
																							B292404	39.62	41.15	0.050			VA05053953	1.53
																							B292405	41.15	42.67	0.026			VA05053953	1.52
1	1	2.0	2.0	45		0.0																	B292406	42.67	43.59	0.136			VA05053953	0.92
1	1	2.0	2.0	45		0.0																	B292407	43.59	44.60	0.083			VA05053953	1.01
																							B292408	44.60	45.72	0.043			VA05053953	1.12
																							B292409	44.60	45.72	0.047	PD/CA		VA05053953	1.12
																							B292410	STANDARD 3C		0.084	3C		VA05053953	
1	1	0.2	0.2	45									1.0										B292411	45.72	47.02	0.067			VA05053953	1.3
																							B292412	47.02	48.26	0.046			VA05053953	1.24
1	1	0.2	0.2	45									2.0										B292413	48.26	49.22	0.063			VA05053953	0.96
1	4	0.2	0.2	45																			B292414	49.22	50.29	0.027			VA05053953	1.07
1	1	0.2	0.2	35		0.0																	B292415	50.29	51.62	0.023			VA05053953	1.33
																							B292416	BLANK		<0.005			VA05053953	
1	1	0.2	0.2	35		0.0																	B292417	51.62	52.14	0.040			VA05053953	0.52
1	4	0.5	0.5	35		0.0																	B292418	52.14	53.34	0.051			VA05053953	1.2
1	1	0.2	0.2	70		0.0							1.0										B292419	53.34	54.05	0.069			VA05053953	0.71
1	6	2.0	3.0	70		0.0							100.0						90.0												
1	1	0.5	0.5	70		0.0																	B292420	54.05	54.86	0.059			VA05053953	0.81
2	1	0.5	1.0	60		0.0																	B292421	54.86	56.39	0.043			VA05053953	1.53
	1	0.5	1.0	60		0.0																	B292422	54.86	56.39	0.036	DUP		VA05053953	1.53
2	1	1.0	1.5	55		0.0							5.0										B292423	56.39	57.91	0.036			VA05053953	1.52
																							B292424	57.91	59.44	0.047			VA05053953	1.53
1	1	0.2	0.2	65		0.0							5.0										B292425	59.44	60.96	0.039			VA05053953	1.52
1	1	3.0	3.0	?		0.0							1.0										B292426	60.96	61.14	0.098		unable to determine angle due to frac & offset.	VA05053953	0.18
																							B292427	61.14	62.48	0.065			VA05053953	1.34
																							B292428	62.48	64.01	0.121			VA05053953	1.53

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 3 of 10	Carbonate
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		67.06	68.58	core even more competent, recovery very good. minor pervasive lim fracs @ 35° and 55°.	1					
10		68.58	74.68	GND is unalt. lim NO longer pervasive, limited to fracs. veinage increasing. GND is unalt, po occurs for first time in hole.	0					
10		74.68	75.01	less recovery, more alt. return of pervasive lim on interval, fracs have as preferred orientation. frac faces of core are reddish brown--likely due to oxpy. aspy present on faces.	2					
10		75.01	80.77	GND alt only as selvages. no pervasive lim, found on frac only. fracs normally at 50°, recovery is good.	0					
10		80.77	82.64	core is dark green in color and easily scratchable, heavily alt to chlorite. fracs are covered in red brown oxide, weathered py. minor dissem aspy. also found in sulphide vnlets. core is fractured and broken w/ reduced recovery.			4			
10		82.64	83.40	core is a very light white-green color. sericite dominant alt type. contact w/ chl section occurs at 65° @ 82.68m on an oxidized sulphide vn. core is fractured randomly, but is less broken. dissem py abundant.		3	2			
10		83.40	84.91	chl alt lessening, no sulphide vns are present.						
10		84.91	91.44	return to unalt GND. heavy lim staining on faces. fracs predominantly @ 50° to CA.	1					
10		91.44	96.84	unalt GND. trace lim stain on frac. ascent after 92.05m, recovery is very good. increase in number and frequency of vns.	0					
10		96.84	98.26	GND becomes crumbly, less competent. sericitic alt present on fracs.		2				
10		98.26	99.21	core becomes clay, green color, alt changes to chl. aspy present on some frac faces. slickensides present overprint aspy--post mineralization.			3			
10		99.21	99.62	unalt GND, good recovery.						
10		99.62	100.16	GND is bleached. mafics are absent. core is white-ser alt.		3				
10		100.16	101.39	core changes from white to green. becomes softer @ 100.98m. 7cm clay gouge unit at 50° to CA. cross cuts qtz vns. possible fault.		2	3			
10		101.39	106.68	unalt GND. frac at 45-50° to CA.						
10		106.68	107.10	GND is green-chl alt. qtz vns are fractured and crosscut by calcite vnlets.			3			
10		107.10	123.10	unalt GND, good recovery. fracs @ 45° and 60°. fracs are filled w/ carbonate from 111.25m-123.10m. vns appear to be dominated by po. selvages are mainly qtz, but chl may also be present. core shows an increase in veinage. @ 115.82m: rounded GND frags w/ pervasive lim -likely from drillers reaming.						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration, 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B292429	62.48	64.01	0.082	PD/CA		VA05053953	1.53
																						B292430	STANDARD 5E		1.436	5E		VA05053953	
2	1	1.0	2.0	45		2.0	q/chl	4	0				1.0									B292431	64.01	65.53	0.054			VA05053953	1.52
2	1	1.0	1.5	45		0.0							1.0									B292432	65.53	67.06	0.160			VA05053953	1.53
5	1	1.5	5.5	45		0.0							5.0					70.0				B292433	67.06	68.58	0.103			VA05053953	1.52
5	1	1.5	4.5	50		0.0					10.0	1.0										B292434	68.58	70.10	0.546			VA05053953	1.52
4	1	1.0	3.0	50		0.0					20.0		5.0									B292435	70.10	71.63	0.065			VA05053953	1.53
																						B292436	BLANK		<0.005			VA05053953	
4	1	1.0	2.0	45		0.0					20.0	1.0										B292437	71.63	73.15	0.074			VA05053953	1.52
2	6	0.5	1.0	40									60.0					70.0				B292438	73.15	74.68	0.806			VA05053953	1.53
1	6	0.2	0.2	55		1.0	chl	3	0	10			60.0					90.0				B292439	74.68	75.01	0.129			VA05053953	0.33
1	1	0.2	0.2	55		0.0																B292440	75.01	76.20	0.058			VA05053953	1.19
5	1	0.2	1.0	55		3.0	qtz	3	0		10.0	0.1										B292441	76.20	77.72	0.035			VA05053953	1.52
5	1	0.2	1.0	55		3.0	qtz	3	0		10.0	0.1										B292442	76.20	77.72	0.123	DUP		VA05053953	1.52
4	1	1.0	3.0	55		0.0							3.0					80.0				B292443	77.72	79.25	0.129			VA05053953	1.53
5	1	1.0	2.6	70	55	2.0	qtz	3	0	3			5.0					40.0				B292444	79.25	80.77	0.162			VA05053953	1.52
4	1	0.5	2.0	60		2.0	chl	4	0		5.0	2.0	2.0					10.0				B292445	80.77	82.30	0.161			VA05053953	1.53
1	6	1.0	1.0	60		0.0				100								60.0				B292446	82.30	82.64	0.645			VA05053953	0.34
7	6	1.5	9.0	55		0.0				100								30.0				B292447	82.64	83.40	0.275			VA05053953	0.76
	1	0.5	0.5	45		6.0	chl	3	0	1	5.0		3.0									B292448	83.40	84.56	0.037			VA05053953	1.16
	1	0.5	0.5	45		6.0	chl	3	0	1	5.0		3.0									B292449	83.40	84.56	0.034	PD/CA		VA05053953	1.16
																						B292450	STANDARD 6F		2.860	6F		VA05053953	
2	1	1.0	1.2	45		0.0							2.0									B292451	84.56	85.34	0.242			VA05053953	0.78
3	1	1.0	1.4	45		1.0	q/chl	3	0		3.0		1.0									B292452	85.34	86.87	0.089			VA05053953	1.53
1	1	1.0	1.0	45		1.0	q/chl	3	0		4.0		2.0									B292453	86.87	88.39	0.083			VA05053953	1.52
3	1	2.0	3.5	45		0.5	qtz	2	0		2.0		0.1									B292454	88.39	89.92	0.061			VA05053953	1.53
2	1	1.0	1.5	40		1.0	qtz	2	0		25.0	2.0										B292455	89.92	91.44	0.058			VA05053953	1.52
																						B292456	BLANK		<0.005			VA05053953	
4	1	1.5	1.5	45		10	q/ser	3	0	26			5.0									B292457	91.44	92.17	0.416			VA05053953	0.73
3	1	1.0	2.5	30	20	0.0				5			2.0									B292458	92.17	92.96	0.145			VA05053953	0.79
4	1	1.5	4.0	45	30	15	q/ser			10			1.0									B292459	92.96	93.69	0.283			VA05053953	0.73
6	1	3.0	6.0	45		2.0	8	2	0		10.0											B292460	93.69	94.49	0.396			VA05053953	0.8
3	1	1.0	2.5	40							1.0	1.0	1.0									B292461	94.49	96.01	0.040			VA05053953	1.52
3	1	1.0	2.5	40							1.0	1.0	1.0									B292462	94.49	96.01	0.041	DUP		VA05053953	1.52
3	1	1.0	1.6	45		0.0					2.0											B292463	96.01	96.84	0.315			VA05053953	0.83
8	1	1.5	5.5	45	30	0.0					5.0		2.0									B292464	96.84	98.26	0.167			VA05053953	1.42
5	1	1.0	5.0	45		5.0	q/chl	4	0	10								70.0				B292465	98.26	99.21	0.313			VA05053953	0.95
1	1	2.0	2.0	50		10	chl	4	0		10.0											B292466	99.21	99.62	0.295			VA05053953	0.41
3	1	1.0	2.0	50		0.0					5.0											B292467	99.62	100.16	0.159			VA05053953	0.54
4	1	1.0	3.0	60	30	0.0					3.0											B292468	100.16	101.39	0.107			VA05053953	1.23
																						B292469	100.16	101.39	0.105	PD/CA		VA05053953	1.23
																						B292470	STANDARD 7G		4.410	7G		VA05053953	
																						B292471	101.39	102.11	0.046			VA05053953	0.72
7	1	1.0	4.5	60	30	0.0					30.0											B292472	102.11	103.63	0.159			VA05053953	1.52
9	1	2.0	6.2	30		1.0	qtz	4	0		10.0	0.1										B292473	103.63	105.16	0.311			VA05053953	1.53
7	1	1.0	5.5	30		1.0	qtz	4	0		5.0	0.1										B292474	105.16	106.68	0.182			VA05053953	1.52
3	1	2.0	6.0	30							1.0											B292475	106.68	107.10	0.091			VA05053953	0.42
																						B292476	BLANK		<0.005			VA05053953	
5	1	1.0	3.0	40		0.2	qtz	3	0		5.0		1.0									B292477	107.10	108.20	0.186			VA05053953	1.1
8	1	1.0	6.5	40	30	4.0	q/chl	3	0		15.0	1.0										B292478	108.20	109.73	0.736			VA05053953	1.53
																						B292479	109.73	111.25	0.301			VA05053953	1.52
9	1	2.0	7.0	40		0.2	qtz	3	0		10.0	1.0										B292480	111.25	112.78	0.197			VA05053953	1.53
6	1	1.0	5.0	40		1.0	qtz	3	0		5.0	1.0										B292481	112.78	114.30	0.455			VA05053953	1.52
6	1	1.0	5.0	40		1.0	qtz	3	0		5.0	1.0										B292482	112.78	114.30	0.255	DUP		VA05053953	1.52

DRILL LOG LEGEND - P1

DATE: 19-20-June-05 PAGE 5 of 10

DRILL HOLE # : DG05-287C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		123.10	126.31	GND is lighter in color, more feldspar, w/ min ser. core becomes marginally softer.		1				
10		126.31	129.54	core becomes softer as ser alt increases.		2				
10		129.54	132.59	core is more competent, ser alt is reduced to fracs only.						
10		132.59	133.76	unalt GND. greyish color, more competent, good recovery.						
		133.76	134.62	GND is dark green in color--chlorite alt. section also contains 3 massive sulphide vns up to 1cm thick @ 40° to CA.			3			
10		134.62	137.74	unalt GND w/ chl on frac faces. fracs @ 45° and 80°. po in vns, aspy in selvages, py on slickensides.						
10		137.74	138.68	core is light green. ser & chl alt. softer & less competent, contains sulphide vnlets; py.		2	2			
10		138.68	143.26	unalt GND, core is fractured and broken, chl is present on frac. the majority of frac angles are random, but 45° and 80° are still present.						
10		143.26	144.78	GND becomes softer, more ser alt present. @ 144.39m: 15cm clay gouge @ 45° to CA. slickensides present--fault.		2				
10		144.78	147.11	fault zone. core is highly alt'd to clays. qtz vns are powdery. GND frags present up to 5cm. the most intense deformation occurs from 146.20m-146.98m. core is black, very coherent clay containing winged (?) qtz eyes, showing a crustal rotation. fault contact @ 45° to CA. @ 146.44m: 5cm qtz frag containing ~15% py; py may have been emplaced during faulting. the py filled fracs appear to stem from the black clay, w/ a thin zone of py in the clay surrounding the qtz frag (~1mm).						
10		147.11	149.35	core is light green in color, soft but competent. fracs are irregular and random. the majority of vning is sulphide vnlets in fracs. py is dominant, but aspy also present.		2	3			
10		149.35	150.88	core is softer & broken and contains less chl and more ser. no sulphide vns, poor recovery.		3	1			
10		150.88	152.40	core regains coherency, more chl, less ser, sulphide vns return.						
10		152.40	153.92	core is again softer and broken, no sulphide vnlets, poor recovery.						
10		153.92	157.92	core regains coherence w/ increase in chl and decrease in ser. sulphide vns and vnlets return. recovery increases. chl/ser contact @ 45°, diss py present.						
10		157.92	159.30	core becomes unalt GND. more competent, good recovery. vns are mostly qtz. fracs @ 40° & 80°.						
10		159.30	162.57	GND alt by ser and chl. core is broken and fracs coated w/ ser. recovery is reduced to ~67%. sulphide vnlets dominant again, fracs are random.						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n
Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	0.5	3.0	40		1.0	qtz	3	0		10.0											B292483	114.30	115.82	0.276			VA05053953	1.52
5	1	1.5	4.0	30		1.0	qtz	3	0		0.1											B292484	115.82	117.39	0.881			VA05053953	1.57
2	1	1.0	1.2	30		0.0					5.0											B292485	117.39	118.87	0.187			VA05053953	1.48
4	1	1.0	2.5	40		0.0					1.0											B292486	118.87	120.40	0.633			VA05053953	1.53
4	1	2.0	5.0	30	40	1.0	chl	3	0		3.0	0.1					0.1					B292487	120.40	121.92	0.171			VA05053953	1.52
3	1	0.2	0.6	30		0.0					10.0											B292488	121.92	123.10	0.220			VA05053953	1.18
																						B292489	121.92	123.10	0.199	PD/CA		VA05053953	1.18
																						B292490	STANDARD 2B		3.450	2B		VA05053953	
2	1	12	0.2	40		0.0					0.1		0.1									B292491	123.10	123.84	0.508			VA05053953	0.74
3	1	0.2	0.2	40		0.0																B292492	123.84	124.97	0.643			VA05053953	1.13
1	1	2.0	2.0	40		0.0					5.0		0.1									B292493	124.97	126.49	0.219			VA05053953	1.52
4	1	3.0	2.5	40		0.0					2.0											B292494	126.49	128.02	0.042			VA05055092	1.53
0																						B292495	128.02	129.54	1.875			VA05055092	1.52
																						B292496	BLANK		<0.005			VA05055092	
2	1	1.0	2.0	40		0.0					2.0		0.1									B292497	129.54	131.06	0.328			VA05055092	1.52
2	1	1.0	1.5	40		0.0					1.0											B292498	131.06	132.59	0.158			VA05055092	1.53
2	1	1.5	2.0	45		0.0					2.0											B292499	132.59	133.76	1.380			VA05055092	1.17
1	6	0.2	0.2	40		0.0				100																			
3	6	0.2	0.6	45		0.0				100								0.0				B292500	133.76	134.62	0.550			VA05055092	0.86
1	1	1.0	1.0	45		0.0				1																			
2	1	1.5	2.0	40		0.0							1.0									B381601	134.62	135.64	1.015		Jump in sample tag #'s is due to switching from old batch to new batch of sample books.	VA05055279	1.02
	1	1.5	2.0	40		0.0							1.0									B381602	134.62	135.64	0.180	DUP		VA05055279	1.02
	1	1.5	2.5	45	60	0.0				1												B381603	135.64	137.16	1.260			VA05055279	1.52
2	1	1.0	1.5	45		0.0				1												B381604	137.16	137.74	0.729			VA05055279	0.58
1	1	1.0	1.0	45		0.0				1			2.0									B381605	137.74	138.68	0.427			VA05055279	0.94
1	6	0.5	0.5	45		0.0				100								60.0											
4	1	1.0	2.5	45		0.0				1			0.1									B381606	138.68	140.21	0.164			VA05055279	1.53
3	1	1.0	2.0	50		1.0	chl	3	0		3.0		0.1									B381607	140.21	141.73	0.524			VA05055279	1.52
2	1	1.0	2.0	45		0.0				5			1.0									B381608	141.73	143.26	0.533			VA05055279	1.53
2	1	1.0	2.0	45		0.0				5			1.0									B381609	141.73	143.26	0.478	PD/CA		VA05055279	1.53
																						B381610	STANDARD 7G		4.620	7G		VA05055279	
1	1	8.0	8.0	50		0.0					0.1	0.1	1.0					60.0				B381611	143.26	144.78	0.613			VA05055279	1.52
0																						B381612	144.78	146.30	0.320			VA05055279	1.52
1	1									15												B381613	146.30	147.11	2.240		qtz is in fault, not a vn but worth noting	VA05055279	0.81
3	6	0.2	0.6	60		0.0				100								60.0				B381614	147.11	147.83	0.639			VA05055279	0.72
2	6	0.2	0.4	60		0.0				100								40.0				B381615	147.83	149.35	0.445			VA05055279	1.52
2	1	1.0	1.2	60		1.0	chl	4	0																				
																						B381616	BLANK		<0.005			VA05055279	
2										0.1												B381617	149.35	150.88	0.062		core too broken for measurements.	VA05055279	1.53
4	6	0.2	0.8	60		0.0				100								70.0				B381618	150.88	152.40	0.434			VA05055279	1.52
1	1	1.0	1.0	45		0.0				0.1																			
1	1	1.0	1.0	45		0.0																B381619	152.40	153.92	0.298			VA05055279	1.52
3	6	0.2	0.6	75		0.0				100								40.0				B381620	153.92	155.45	0.116			VA05055279	1.53
3	1	1.5	2.5	45		0.0				15								20.0				B381621	155.45	156.97	0.354			VA05055279	1.52
	1	1.5	2.5	45		0.0				15								20.0				B381622	155.45	156.97	0.226	DUP		VA05055279	1.52
	6	0.2	0.8	75		0.0				100								70.0				B381623	156.97	157.42	0.443			VA05055279	0.45
6	1	1.0	3.5	70	85	6.0	q/chl	5	0				1.0									B381624	157.42	158.50	0.665			VA05055279	1.08
1	6	0.2	0.2	60		0.0				100								20.0											
2	1	1.0	1.6	60		0.0							1.0									B381625	158.50	159.30	0.129			VA05055279	0.8
2	1	0.2	0.4	70		0.0																B381626	159.30	160.02	0.680			VA05055279	0.72
7	1	2.0	5.5	60		1.0	chl	4	0		5.0		1.0									B381627	160.02	161.54	0.516			VA05055279	1.52
1	6	0.2	0.2	80		0.0				100																			

DRILL LOG LEGEND: P1	DATE: 19-20-June-05	PAGE 7 of 10	
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		162.57	165.32	core is more intensely alt to clays. core is crumbly, soft and contains qtz eyes, and is coherent until disturbed.						
10		165.32	166.12	core becomes less alt, much more coherent, recovery is greatly increased. sulfide vnlets no longer present.						
10		166.12	174.04	unalt GND, core is grey-blue. recovery is excellent, vns are predominantly qtz.						
10		174.04	175.01	core is alt to ser and chl, light green color. @ 174.14m: 6cm grey qtz vn @ 50°, slickensides on end of vn.						
10		175.01	183.46	unalt GND, recovery excellent, fracs @ 30°.						
10		183.46	184.73	core is dark green in color, chl alt. contains massive sulphide vnlets--py. fracs @ 50°, as are the vns. core is fine grained.			2			
10		184.73	185.17	core appears more granular, alt is more intense, chl and ser present. soft but coherent core. massive sulphide vns present @ 184.73m & 185.17m, flanking the alt zone.		2	2			
10		185.17	186.63	GND becomes med-grained, still has green color--chl. fracs continue at 50°.			2			
10		186.63	187.45	less alt GND, starts fine-grained & changes gradually to med-gr.						
10		187.45	191.52	unalt med-gr GND, frac at high angle 75°.						
10		191.52	192.75	zone of chl alt. core is green and scratches easily. sulfide vnlets fill some fracs.			2			
10		192.75	213.84	unalt GND, fine-gr, frac @ 45° and 50°. vns follow fracs, dominant sulfide is po.						
10		213.84	216.96	unalt GND, med-gr. @ 213.86m: 0.2cm fault @ 65° to CA. py present overprinting slickensides. 15cm zone of chl alt around fault.						
10		216.96	219.46	fine-gr GND.						
				EOH		-				

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	1.5	2.0	60		0.0				1												B381628	161.54	162.57	0.562			VA05055279	1.03
2	1	1.5	2.0	60		0.0				1												B381629	161.54	162.57	0.734	PD/CA		VA05055279	1.03
																						B381630	STANDARD 3C		0.093	3C		VA05055279	
3	6	0.4	0.6	40		0.0				90			10.0					60.0				B381631	162.57	164.02	1.260			VA05055279	1.45
3	1	1.0	2.2	40		0.0				3												B381632	164.02	165.32	1.625			VA05055279	1.3
2	1	0.5	0.7	40		0.0				0.1												B381633	165.32	166.12	0.242			VA05055279	0.8
6	1	1.0	4.5	45							5.0											B381634	166.12	167.64	0.674			VA05055279	1.52
1	4	0.5	0.5	30																									
7	1	3.0	5.0	50		0.0					5.0											B381635	167.64	169.16	0.394			VA05055279	1.52
																						B381636	BLANK		<0.005			VA05055279	
5	1	1.0	3.8	50		0.0				5	5.0		1.0									B381637	169.16	170.69	0.082			VA05055279	1.53
1	6	0.5	0.5	50		0.0				70			30.0					5.0				B381638	170.69	172.21	0.253			VA05055279	1.52
3	1	1.0	2.5	50		0.0					10.0																		
2	1	1.0	1.5	30		0.0							0.1									B381639	172.21	173.74	0.200			VA05055279	1.53
2	1	0.2	0.4	30							5.0											B381640	173.74	174.04	0.075			VA05055279	0.3
2	1	6.0	6.5	50		0.0				10												B381641	174.04	175.01	0.690			VA05055279	0.97
2	1	6.0	6.5	50		0.0				10												B381642	174.04	175.01	1.005	DUP		VA05055279	0.97
1	1	0.2	0.2	25		0.0				3	5.0											B381643	175.01	176.30	0.169			VA05055279	1.29
1	1	6.0	6.0	50		2.0	chl			10	3.0											B381644	176.30	177.43	0.747			VA05055279	1.13
2	1	1.0	1.0	50		0.0					1.0											B381645	177.43	178.93	0.574			VA05055279	1.5
1	1	3.0	3.0	50						2	7.0	1.0										B381646	178.93	179.86	11.850			VA05055279	0.93
3	1	0.2	0.6	40		0.0					1.0	0.1										B381647	179.86	181.36	0.236			VA05055279	1.5
	1	1.0	4.0	60		0.0					5.0											B381648	181.36	182.88	0.246			VA05055279	1.52
	1	1.0	4.0	60		0.0					5.0											B381649	181.36	182.88	0.342	PD/CA		VA05055279	1.52
																						B381650	STANDARD 4D		0.465	4D		VA05055279	
1	1	1.0	1.0	50						1	1.0											B381651	182.88	183.46	0.953			VA05055279	0.58
3	6	0.2	0.6	55		0.0				100								5.0				B381652	183.46	184.73	0.131			VA05055279	1.27
1	6	2.0	2.0	55		0.0				100												B381653	184.73	185.17	1.060			VA05055279	0.44
2	1	0.2	0.4	50		0.0																B381654	185.17	186.63	0.869			VA05055279	1.46
1	1	1.0	1.0	45		0.0				0.1												B381655	186.63	187.45	0.545			VA05055279	0.82
																						B381656	BLANK		<0.005			VA05055279	
2	1	0.2	0.4	50		0.0					5.0											B381657	187.45	188.98	0.324			VA05055279	1.53
2	1	0.2	0.4	50		0.0					2.0											B381658	188.98	190.50	0.654			VA05055279	1.52
4	1	1.0	1.6	60		1.0	chl	3	0		5.0	0.1	0.1									B381659	190.50	191.52	1.035			VA05055279	1.02
4	1	3.0	6.0	60		0.0							20.0									B381660	191.52	192.72	4.550			VA05055279	1.2
1	1	0.2	0.2	50		0.2	qtz				0.1											B381661	192.72	193.55	0.789			VA05055279	0.83
1	1	0.2	0.2	50		0.2	qtz				0.1											B381662	192.72	193.55	1.765	DUP		VA05055279	0.83
2	1	1.0	1.0	30		0.0																B381663	193.55	195.07	0.855			VA05055279	1.52
7	1	1.0	5.0	60	30	0.0					3.0											B381664	195.07	196.60	0.654			VA05055279	1.53
3	1	1.0	2.0	53		1.0	qtz	3	0		10.0	2.0						10.0				B381665	196.60	198.12	0.503			VA05055279	1.52
3	1	2.0	0.6	50		0.0																B381666	198.12	199.64	0.193			VA05055279	1.52
5	1	0.2	1.0	65	40	0.2	qtz	3	0													B381667	199.64	201.17	0.570			VA05055279	1.53
3	1	0.2	0.6	60		0.2	qtz	3	0		3.0											B381668	201.17	202.69	0.158			VA05055279	1.52
3	1	0.2	0.6	60		0.2	qtz	3	0		3.0											B381669	201.17	202.69	0.206	PD/CA		VA05055279	1.52
																						B381670	STANDARD 3C		0.090	3C		VA05055279	
3	1	1.0	3.0	40		0.2	qtz	3	0		0.1											B381671	202.69	204.22	0.312			VA05055279	1.53
4	1	0.5	2.0	70		0.0							1.0									B381672	204.22	205.74	1.020			VA05055279	1.52
3	1	1.0	1.7	60		0.2	qtz	3	0		3.0											B381673	205.74	207.26	1.605			VA05055279	1.52
5	1	1.0	2.7	60							5.0		10.0									B381674	207.26	208.79	4.360			VA05055279	1.53
6	1	1.0	3.5	65		0.0					5.0	1.0										B381675	208.79	210.31	0.388			VA05055279	1.52
																						B381676	BLANK		<0.005			VA05055279	
	1	2.0	3.0	55		4.0	q/chl	3	0		1.0											B381677	210.31	211.84	1.395			VA05055279	1.53
1	1	2.8	2.5	50		0.0				5												B381678	211.84	213.36	3.810			VA05055279	1.52
1	4	0.2	0.2	25																									
2	1	0.2	0.4	65		0.0				5												B381679	213.36	214.88	0.353			VA05055279	1.52
2	1	0.2	0.4	65		0.0					10.0											B381680	214.88	216.41	1.710			VA05055279	1.53
3	1	0.2	0.6	65							5.0											B381681	216.41	217.93	1.590			VA05055279	1.52
3	1	0.2	0.6	65							5.0											B381682	216.41	217.93	1.225	DUP		VA05055279	1.52

DRILL LOG LEGEND - P1	DATE: 19-20-June-05	PAGE 9 of 10	
DRILL HOLE # : DG05-287C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation					From	To					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
3	1	0.2	0.6	65							5.0											B381683	217.93	219.46	1.060			VA05055279	1.53
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-288C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 905m

BEARING: 000 | DIP: -50°

DATE STARTED: 20-Jun-05 | DATE COMPLETED: 22-Jun-05

LOGGED BY: Terry Croteau July 1-5, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459109 NORTHING: 7099040

COORD SYSTEM: NAD 83: EASTING: 458991 NORTHING: 7099224

NAD 27 (CORRECTED for historic grid): EASTING: 459079 NORTHING: 7099050

SECTION LINE(historic grid): 459079

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 10.36m

Deviation:

Casing: 10.36m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary. EOH corrected by DH (Nov).

SAMPLING DETAILS

Sample Sequence: B380453-B380610

Requisition #: MASP448STRGOL.05Q Date Shipped: July 8, 2005

Lab Record #: VA05060563 Date Received: 21-July-2005

Sample Sequence: B381717-B381878

Requisition #: MASP448STRGOL.05Q Date Shipped: July 8, 2005

Lab Record #: VA05058631 Date Received: 15-July-2005

Special Note: Samples divided between lab records - entire hole between these two.

Duplicates:	380462, 380482, 380502, 380522, 380542, 380562, 380582, 380602
Preparation Duplicate/ Check Assay:	380449, 380469, 380489, 380509, 380529, 380549, 380569, 380589, 380609
Standards:	380450 (3C), 380470 (2B), 380490 (7G), 380510 (5E), 380530 (3C), 380550 (3C), 380570 (4D), 380590 (4D), 380610 (2B)
Blanks:	380456, 380476, 380496, 380516, 380536, 380556, 380576, 380596

FROM	TO	LITHOLOGY
10.36	195.37	GND

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.0	350.5	-51.0	016.5	017.5
120.0	359.1	-52.0	025.1	026.1
195.0	356.0	-56.6	022.0	023.0

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 1 of 8			
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered		Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 10.36			Casing; recovered 30cm of GND. Pervasive lim, half of the core is altered to clay, oxidized aspy vein present	3					
10	10.36 - 195.37			GND - See previous logs for description						
10		10.36	12.19	Core is soft but coherent. Light grey in color. Oxidized sulphide veins are present throughout. Aspy is dominant sulphide. No lim present				3		
10		12.19	13.72	Core is still soft, but becomes broken into gravel sized pieces. Minor lim on frac. Recovery is poor.	1			3		
10		13.72	15.24	Core becomes more solid, clay alt'n present on fractures. Fractures show no preferred orientation. No lim present	1			2		
10		15.24	18.29	GND is light grey in color and highly fractured. Fractures normally @ 45° and 120°. Clay alteration on fractures is greatly reduced. No visible veins present.	1			1		
10		18.29	21.63	First occurrence of pervasive lim. Fractures are at 30° and 70°. Sulphide veins present are generally found at 30° to CA. The number and size of the sulphide veins have increased. Core is still broken, but most (85%) of the pieces are greater than 10cm. Recovery still poor.	3					
10		21.63	29.32	GND - lim is pervasive and heavily stains fractures. Clay alt'n is also common on fracture faces. Core is fractured and broken with 30% gravel size, 50% up to 10 cm and 20% greater than 10 cm. Fractures occur at 50° and 130° to CA. Sulphide veins continue to be present. @22.06m - 2cm sulphide vein at 30° to CA. Contact with quartz vein. Aspy dominant sulphide.	3			1		
10		29.32	30.48	Core is much more competent, good recovery. Less pervasive lim, and a decrease in sulphide veins.	2					
10		30.48	32.00	Core becomes fragmented into gravel sized pieces (80%) and pieces up to 10cm (20%). Pervasive lim is almost absent, but fractures are coated.	1					
10		32.00	34.13	GND is soft but coherent. Clay alt'n present, core has sugary texture. Pervasive lim increased as well as that on frac faces. Fractures at 20° and 100°.	3			2		
10		34.13	34.43	End of pervasive limonite						
		34.43	36.58	GND has become silicified. Blue-grey color. Disseminated aspy, and py found throughout. There is no visible contact with unalt'd core at beginning of interval. Contact at end, 70° to CA.						
10		36.58	41.15	Unaltered GND. Dark grey color, fractures at 60° and 110°. Euhedral aspy crystals found on frac faces. Veins run parallel to fractures. Core is broken in places with 20% of pieces <10cm.						
10		41.15	45.72	GND is silicified. Grey green color. Highly fractured and broken. Euhedral aspy crystals growing on faces. Most pieces (85%) are gravel sized, very angular.			2			Si
10		45.72	50.89	Unaltered GND. Dark Grey color, more competent and increased recovery. Small qtz veins present (most <.5 cm) as sheeted vein system. Aspy can still be found on most frac faces. @48.62m - 10cm clay altered section. Contact at 50° to CA			1			
10		50.89	51.82	Clay alt'd GND is granular with abundant euhedral aspy crystals.				2		
10		51.82	52.72	Unaltered GND. Fractured and broken (80% > 5 cm)						
10		52.72	54.86	GND is bleached, mafics almost completely absent. Aspy is present as fracture fill, in veins, and as diss euhedral crystals. Core is broken 60% < 10 cm. Fractures at 40° and 60°. Color likely due to veining.		3				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	6	0.2	0.4	40		0.0							100.0					70.0				B380443	10.06	10.67	0.057			VA05060563	0.61
6	6	0.2	1.2	50		0.0							100.0					70.0				B380444	10.67	12.19	0.377			VA05060563	1.52
0																						B380445	12.19	13.72	0.029			VA05060563	1.53
1	6	0.2	0.2	50		0.0							100.0					70.0				B380446	13.72	15.24	0.028			VA05060563	1.52
0																						B380447	15.24	16.76	0.078			VA05060563	1.52
																						B380448	16.76	18.29	0.317			VA05060563	1.53
0																						B380449	16.76	18.29	0.322	PD/CA		VA05060563	1.53
																						B380450	STANDARD 3C		0.100	3C		VA05060563	
5	6	0.2	0.2	50		0.0							100.0					70.0				B380451	18.29	19.81	0.230			VA05060563	1.52
2	6	1.5	1.7	50		0.0							100.0					10.0				B380452	19.81	21.34	0.354			VA05060563	1.53
2	6	0.2	0.4	40		0.0																B380453	21.34	22.02	0.128			VA05060563	0.68
2	6	2.0	3.0	30		0.0							100.0					10.0				B380454	22.02	22.10	1.815			VA05060563	0.08
1	6	0.2	0.2	40		0.0							100.0					10.0				B380455	22.10	22.86	0.059			VA05060563	0.76
																						B380456	BLANK		<0.005			VA05060563	
2	6	0.2	0.4	40		0.0							100.0					25.0				B380457	22.86	24.38	0.069			VA05060563	1.52
1	6	0.2	0.2	40		0.0							100.0					10.0				B380458	24.38	25.91	0.076			VA05060563	1.53
1	1	1.5	1.5	40		0.2	q	3	0				15.0									B380459	25.91	27.43	0.047			VA05060563	1.52
2	1	0.5	0.7	40		0.2	q	3	0				40.0									B380460	27.43	28.86	0.083			VA05060563	1.43
2	6	0.2	0.4	40		0.0							100.0					10.0				B380461	28.86	30.48	0.098			VA05060563	1.62
2	6	0.2	0.4	40		0.0							100.0									B380462	28.86	30.48	0.080	DUP		VA05060563	1.62
2	6	0.2	0.4	40		0.0							100.0					25.0				B380463	30.48	32.00	0.136			VA05060563	1.52
3	1	0.2	0.6	30		0.2	q	3	0				10.0									B380464	32.00	33.53	0.073			VA05060563	1.53
0																						B380465	33.53	34.43	0.072			VA05060563	0.90
2	6	0.2	0.4	40									100.0									B380466	34.43	35.05	0.127			VA05060563	0.62
2	6	0.2	0.4	40									100.0									B380467	35.05	36.58	0.057			VA05058631	1.53
1	1	4.0	4.0	30		0.0							50.0									B380468	36.58	38.10	0.382			VA05058631	1.52
1	1	4.0	4.0	30		0.0							50.0									B380469	36.58	38.10	0.354	PD/CA		VA05058631	1.52
																						B380470	STANDARD 2B		3.390	2B		VA05058631	
2	1	0.2	0.4	60		0.0							15.0									B380471	38.10	39.60	0.082			VA05058631	1.50
11	1	0.2	2.2	60		0.2	q	3	0				10.0					25.0				B380472	39.60	41.15	0.070			VA05058631	1.55
3	6												100.0									B380473	41.15	42.67	0.053		Vein broken into pieces	VA05060563	1.52
4	1	0.5											10.0									B380474	42.67	44.20	0.124		Vein broken into pieces	VA05060563	1.53
2	6	0.2											100.0									B380475	44.20	45.72	0.132		Vein broken into pieces	VA05060563	1.52
																						B380476	BLANK		<0.005			VA05060563	
7	1	0.2	1.4	60	120	0.2	q	3	0				20.0									B380477	45.72	47.24	0.171			VA05060563	1.52
6	1	0.2	1.2	60		0.2	q	3	0				10.0									B380478	47.24	48.77	0.143			VA05058631	1.53
4	1	0.2	0.8	60		0.2	q	3	0				10.0									B380479	48.77	50.29	0.102			VA05058631	1.52
2	1	0.5	0.7	60		0.2	q	3	0				5.0									B380480	50.29	51.82	0.133			VA05058631	1.53
3	1	0.5	1.2	30		0.2	q	3	0				5.0									B380481	51.82	52.72	0.466			VA05058631	0.90
3	1	0.5	1.2	30		0.2	q	3	0				5.0									B380482	51.82	52.72	0.543	DUP		VA05058631	0.90
6	6	0.2	1.2	40									100.0					25.0				B380483	52.72	53.34	0.740			VA05058631	0.62
10	6	0.2	2.0	40									100.0					25.0				B380484	53.34	54.86	0.737			VA05058631	1.52

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 3 of 8	
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescen
5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		54.86	56.00	GND is less bleached, bt becomes visible. Core still contains significant aspy veinlets and grey qtz veins with above avg concentrations. @55.22m core is broken into gravel sized pieces with aspy on fractures.		1				
10		56.00	59.44	GND in larger pieces, dark grey in color. Carbonate on frac surfaces, and aspy veinlets fewer in number. Euhedral aspy crystals still present on many frac faces.				1	1	
10		59.44	60.98	GND is soft, and altered to clay - sugary texture. Core breaks when handled. Recovery is poor. Diss aspy present.		1		2		
10		60.98	65.53	GND more coherent, less clay alt'n - found only on fracture. High aspy concentration in veins. Fractures @ 10°, 40° and 160°. Recovery is good.				1		
10		65.53	68.58	Core is broken and 80% is gravel sized or smaller, 20% > 5cm. Clay alteration has left much of the core with a sugary texture. Diss aspy present. Recovery is poor.				3		
10		68.58	70.10	Very poor recovery. Intense clay alteration. Core is broken into gravel sized pieces (20%) and smaller (80%). Sugary texture, looks like broken concrete. Aspy with slickensides found on several faces.				4		
10		70.10	71.63	Clay alteration is less intense. Recovery increased. Core is still broken into gravel sized (40%) and larger (50%). Diss aspy can be found within fractures at 50° and 110°.				2		
10		71.63	76.20	Good recovery. Competence is greatly increased. Fractures at 30°, 50° and 140°. Carbonate fills many fractures and is found on frac faces. Aspy and chl also found on frac surfaces.			1	1	1	
10		76.20	77.72	Core is broken into gravel sized (85%) and larger pieces. Diss aspy present. Chl on frac as well as carb. Sulphide veins are oxidized.			1		1	
10		77.72	79.25	Core is still broken, but pieces are larger. Some faces contain aspy with slickensides. Carb and chl still on faces			1		1	
10		79.25	82.30	Core is light green in color and shows increased veining. Carb veins present and selvages on qtz are cb. Frac at 60° and 105°.			2		1	
10		82.30	90.37	Core is dark grey, less carb alt'n present. Chl still present on frac. Veins are still small (< 0.2 cm) with above avg aspy percentages. @85.04m, aspy on face showing slickensides. @85.14m, 6cm gouge. Qtz eyes and GND frags present. No visible contact; @85.24m, 7cm gouge @ 40° to CA. Qtz eyes and GND frags present.			2		1	
10		90.37	94.49	Core is light green color with diss aspy found throughout. Sulphide veinlets are common. Carb alt'n in core, but more present on frac faces. Fractures at 60° and 140°.		1	3		2	
10		94.49	98.31	Core is grey, less chl alt. Carb alt is still present on frac. There is a reduction in the number of veins and sulphides present. @97.01 7 cm bleached section with diss aspy -> likely selvage, but no vein visible		1	1		1	
10		98.31	99.06	Core is green (<10% mafics), fractures filled with aspy. Selvages also contain aspy. Increase in sulphide veins.			3			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	6	0.2	1.0	40		0.0							100.0									B380485	54.86	56.00	0.697			VA05058631	1.14
5	6	0.2	1.0	40		0.0							100.0									B380486	56.00	56.37	0.096			VA05058631	0.37
2	6	0.2	0.4	40		0.0							100.0									B380487	56.37	57.71	0.148			VA05060563	1.34
4	1	1.0	1.6	50		0.2	q	3	0				15.0									B380488	57.71	59.44	0.178			VA05060563	1.73
4	1	1.0	1.6	50		0.2	q	3	0				15.0									B380489	57.71	59.44	0.172	PD/CA		VA05060563	1.73
																						B380490	STANDARD 7G		4.550	7G		VA05060563	
4	6	0.2											100.0									B380491	59.44	60.98	0.108		Vein broken into pieces	VA05060563	1.54
3	1	1.0	2.5	40		0.5	q	3	0				15.0									B380492	60.98	62.48	0.172			VA05058631	1.50
3	6	0.2	0.6	40									100.0									B380493	62.48	64.01	0.068			VA05058631	1.53
3	1	0.5	0.9	50		0.2	q	4	0				20.0									B380494	64.01	65.53	0.156			VA05058631	1.52
1	6																					B380495	65.53	67.06	0.091		Interval intensel altered to clay	VA05058631	1.53
																						B380496	BLANK		<0.005			VA05058631	
2	1	0.2	0.4	50		0.2	q	3	0				5.0									B380497	67.06	68.58	0.143			VA05058631	1.52
3	1	0.2	0.6										10.0									B380498	68.58	70.10	0.122		Vein broken into pieces	VA05058631	1.52
3	6	0.2	0.6	50									10.0									B380499	70.10	71.63	0.130		Vein broken into pieces	VA05058631	1.53
6	1	1.0	2.4	50		0.2	q	4	0				5.0									B380500	71.63	73.15	0.224			VA05058631	1.52
3	1	0.5	0.9	50	160	2.0	q	3	0				10.0									B380501	73.15	74.68	0.280		Most aspy found in slevages	VA05060563	1.53
3	1	0.5	0.9	50	160	2.0	q	3	0				10.0									B380502	73.15	74.68	0.278	DUP		VA05060563	1.53
6	1	0.2	1.2	50		0.5	q	3	0				5.0									B380503	74.68	76.20	0.377			VA05060563	1.52
1	6	0.2	0.2	50									100.0																
2	1	0.5	0.7	50		0.2	chl	4	0				5.0									B380504	76.20	77.72	0.361			VA05060563	1.52
3	1	0.5	0.9	50		3	q	4	0				5.0									B380505	77.72	79.25	0.216		Aspy in selvages	VA05060563	1.53
10	1	0.5	1.7	50		0.2	cb	4	0				10.0									B380506	79.25	80.77	0.206		Aspy in selvages and veins	VA05060563	1.52
4	1	0.2	1.1	50		1.0	cb	4	0				5.0									B380507	80.77	82.30	0.114			VA05060563	1.53
2	4	0.5	1.0	30		0.0																					Diss aspy found near cb vein		
2	1	0.2	0.4	60		0.2	q	4	0				1.0									B380508	82.30	83.82	0.133			VA05060563	1.52
2	1	0.2	0.4	60		0.2	q	4	0				1.0									B380509	82.30	83.82	0.140	PD/CA		VA05060563	1.52
																						B380510	STANDARD 5E		1.470	5E		VA05060563	
4	1	0.2	0.8	60		0.2	q	3	0				5.0									B380511	83.82	85.34	0.248			VA05060563	1.52
3	1	0.2	6.0	60		0.2	q	3	0				1.0									B380512	85.34	86.51	0.089			VA05060563	1.17
1	1	0.2	0.2	60		0.2	q	3	0				1.0									B380513	86.51	88.39	0.201		Veins broken, aspy in selvage	VA05060563	1.88
1	1	0.5	0.5	50		0.2	cb	3	0				1.0									B380514	88.39	89.92	0.302			VA05060563	1.53
1	1	0.2	0.2	50		0.2	q	4	0				1.0									B380515	89.92	90.37	0.239			VA05060563	0.45
																						B380516	BLANK		<0.005			VA05060563	
4	1	1.0	1.4	50		0.5	cb	4	0				10.0									B380517	90.37	91.44	0.328			VA05060563	1.07
2	1	0.2	0.4	50		1.0	q	3	0				3.0									B380518	91.44	92.96	0.330		Aspy in selvages	VA05060563	1.52
5	1	0.2	1.7	50							0.1		3.0									B380519	92.96	94.49	0.488			VA05060563	1.53
4	1	0.2	0.8	50	140	0.2	q	2	0				0.1									B380520	94.49	96.01	0.316			VA05060563	1.52
4	1	0.2	0.8	50		2.0	q	4	0				5.0									B380521	96.01	97.54	0.562		Aspy in selvage and vein	VA05060563	1.53
4	1	0.2	0.8	50		2.0	q	4	0				5.0									B380522	96.01	97.54	0.437	DUP		VA05060563	1.53
4	1	0.2	0.8	50		0.2	q	2	0				1.0									B380523	97.54	98.31	0.577			VA05060563	0.77
4	6	1.0	1.6	50									100.0									B380524	98.31	99.06	0.325			VA05060563	0.75
2	1	0.5	0.7	50		0.5	q	4	0				0.1																

DRILL LOG LEGEND - P1	DATE: June 20 - 22, 2005 PAGE 5 of 8		
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		99.06	108.60	GND is light grey color with fractures at 50° and 140°. Fracture faces are covered with carb and ser. Numerous aspy veinlets present, but a decline in qtz veins. Aspy with slickensides present on some fractures (5%) others (50%) have euhedral aspy crystals.						
10		108.60	109.73	Core is light green color and contains diss aspy. Fractures show ser and carb alt'n and are at 40° and 120°. Diss py present. @109.23m, 3cm heavily altered to clay at 40° to CA. Slickensides present.		1	2		1	
10		109.73	112.78	Core becomes broken, with more clay alteration on broken surfaces. Chl alt'n is reduced. Aspy with slickensides found on some frac surfaces.		1	1		2	
10		112.78	113.40	Core is light green color with ser and carb on frac surfaces. Diss aspy present as well as an increase in the number of veins and % sulphides.		1	2		1	
10		113.40	118.34	Return to dark grey GND. Rock is fractured and broken. Fractures show euhedral aspy crystals, 5% have aspy with slickensides. Carb alt'n still occurs on most (80%) frac faces. Veins continue to be small and are found in sheeted sets.					1	
10		118.34	119.12	Intense clay alteration follows low angle fractures (relative to CA) 0-20° and 160-180°. Core is soft and contains diss aspy.		3	1	2	2	
10		119.12	123.44	GND is light grey in color and chl alt'n is common on frac faces. Carb veins and veinlets become more numerous, cross cutting qtz and sulphide veins at 140° and 170°.		1	2	1	1	
10		123.44	129.54	Alteration is reduced, minor chl and ser on frac surfaces. Sheeted vein sets are present. Veins are small (0.2 cm) and most contain aspy.		1	1		1	
10		129.54	131.06	Core is green, increased chl alt'n. Rock is soft but competent. Veins are larger in this section and sulphide content is higher.			2		1	
10		131.06	134.11	Core returns to dark grey color. Sheeted vein sets more frequent @ 45°. Carb veinlets crosscut at 175°.					1	
10		134.11	141.73	The end of the sheeted veins. Carb filled fractures are common. Fractures are at 30° and 145° to CA. GND is dark grey in color. Recovery is good. @140.11m, clayey gouge; qtz eyes and GND frags present.					2	
10		141.73	143.26	GND is greenish color with less carb alt and veins. Ser and chl on frac surfaces. Fractures at 60° and 165°.		1	2	1		
10		143.26	149.35	Unaltered GND. Dark grey color. Most (95%) of veins are carb veins. Fractures also filled with carb running at 20°, 40°, 70° and 170°. Slickensides on frac surface with minor aspy showing same feature.						

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6	60		0.2	q	3	0				5.0									B380525	99.06	100.58	0.303			VA05060563	1.52
4	6	0.2	0.8	60									100.0									B380526	100.58	102.11	0.174			VA05058631	1.53
4	1	0.2	8.0	60		0.2	q	3	0				5.0									B380527	102.11	103.63	0.131			VA05058631	1.52
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380528	103.63	105.16	0.157			VA05058631	1.53
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380529	103.63	105.16	0.155	PD/CA		VA05058631	1.53
																						B380530	STANDARD 3C		0.106	3C		VA05058631	
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380531	105.16	106.68	0.197			VA05060563	1.52
7	6	0.2	1.4	60									100.0																
3	1	0.2	0.6	60		0.2	q	3	0				0.1									B380532	106.68	108.20	0.155			VA05060563	1.52
1	1	0.2	0.2	60		0.2	q	3	0													B380533	108.20	108.60	0.089			VA05060563	0.40
3	1	0.2	0.6	60		0.2	chl	3	0				5.0									B380534	108.60	109.73	0.184			VA05060563	1.13
																						B380535	109.73	111.25	0.244			VA05060563	1.52
3	1	0.2	0.6	60		0.2	q	4	0				1.0									B380536	BLANK		<0.005			VA05060563	
1	1	0.5	0.5	40									0.1									B380537	111.25	112.78	0.186		Veins at 60 deg have higher sulfide content	VA05060563	1.53
6	1	1.0	3.7	60	40	0.2	chl	3	0				10.0									B380538	112.78	113.40	0.261			VA05060563	0.62
2	1	0.5	0.7	60		0.2	q	4	0				1.0									B380539	113.40	114.30	0.181			VA05060563	0.90
4	1	0.2	0.8	60		0.2	q	4	0				0.1									B380540	114.30	115.82	0.123			VA05058631	1.52
4	1	0.5	1.1	60		0.2	q	4	0				3.0									B380541	115.82	117.35	0.130			VA05058631	1.53
4	1	0.5	1.1	60		0.2	q	4	0				3.0									B380542	115.82	117.35	0.150	DUP		VA05058631	1.53
9	1	0.2	1.8	50	170	0.2	q	4	0				5.0									B380543	117.35	118.34	0.133			VA05058631	0.99
2	1	0.2	0.4	50		0.5	q	4	0				3.0									B380544	118.34	119.12	0.173			VA05060563	0.78
2	6	0.2	0.4	40									100.0					25.0				B380545	119.12	120.40	0.191			VA05060563	1.28
1	4	0.5	0.5	20																									
1	1	0.2	0.2	40	30	0.2	q	2	0				3.0									B380546	120.40	121.92	0.138			VA05060563	1.52
7	1	0.2	1.4	45		0.2	q	2	0				3.0									B380547	121.92	123.44	0.303			VA05060563	1.52
6	1	0.2	1.2	45		0.1	q	2	0				5.0									B380548	123.44	124.97	0.188			VA05060563	1.53
6	1	0.2	1.2	45		0.1	q	2	0				5.0									B380549	123.44	124.97	0.199	PD/CA		VA05060563	1.53
																						B380550	STANDARD 3C		0.098	3C		VA05060563	
2	1	0.5	0.7	45		0.2	q	3	0				5.0									B380551	124.97	126.49	0.067			VA05060563	1.52
6	1	0.2	0.2	45		0.2	q	4	0				3.0									B380552	126.49	128.52	0.142			VA05060563	2.03
4	1	0.2	0.8	45		0.2	q	3	0				3.0									B380553	128.52	129.54	0.123			VA05058631	1.02
8	1	2.0	2.8	45		0.2	q	2	0				5.0					25.0				B380554	129.54	131.06	0.178			VA05058631	1.52
21	1	0.2	4.2	40		0.2	q	4	0				1.0									B380555	131.06	132.59	0.124			VA05058631	1.53
																						B380556	BLANK		0.009			VA05058631	
21	1	0.2	4.2	40		0.2	q	4	0				1.0									B380557	132.59	134.11	0.169			VA05058631	1.52
8	1	0.2	1.6	40									0.1									B380558	134.11	135.64	0.157			VA05058631	1.53
7	1	0.2	1.4	40		0.2	q	2	0				1.0									B380559	135.64	137.16	0.091			VA05058631	1.52
7	1	0.2	1.4	40		0.2	q	3	0				0.1									B380560	137.16	138.68	0.046			VA05060563	1.52
2	1	0.2	0.4	40		0.2	q	4	0				0.1									B380561	138.68	140.21	0.056			VA05060563	1.53
2	1	0.2	0.4	40		0.2	q	4	0				0.1									B380562	138.68	140.21	0.072	DUP		VA05060563	1.53
7	1	0.2	1.4	40		0.2	q	3	0				1.0									B380563	140.21	141.73	0.105			VA05060563	1.52
2	1	0.2	0.4	40									0.1									B380564	141.73	143.26	0.029			VA05060563	1.53
5	4	0.5	1.1	30																		B380565	143.26	144.78	0.035			VA05060563	1.52
3	4	0.2	0.6	30																		B380566	144.78	146.30	0.027			VA05060563	1.52
4	4	0.2	0.8	30	170																	B380567	146.30	147.83	0.017			VA05060563	1.53
4	1	0.2	0.8	30		0.2	q	2	0				0.1									B380568	147.83	149.35	0.028			VA05060563	1.52
4	1	0.2	0.8	30		0.2	q	2	0				0.1									B380569	147.83	149.35	0.029	PD/CA		VA05060563	1.52

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 7 of 8		
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMQN = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		149.35	151.49	Reduction in carb veins, return to qtz veins. Chl alt'n dominant. Fractures occur at 40° and 95°.		1	2		1	
10		151.49	153.92	Rock is light grey green color, and shows clay alt'n. Qtz eyes and GND pieces are present indicating hydrothermal alt'n. Core is highly fractured and broken into gravel sized pieces (45%) and >5cm (55%). Gouge contacts @ 30° to CA @ 152.40m,for 8cm.		1	1	2		
10		153.92	157.74	Core is green and peach coloured. Selvages and fractures are filled with K-spar and carbonate. Py makes its first appearance as a sulphide vein @ 154.72m. Frac at 40° and 110° @157.11m, 10cm gouge @ 60° to CA, followed by diss aspy in 8cm of intense chl alt'n.			2		2	3
10		157.74	161.54	Dark grey GND with minor ser, carb and chl alt'n on fracture faces. Fractures at 30°, 70°, and 170°. Veins crosscut by 170° fractures. Euhedral aspy crystals present on frac faces @160.02m to 161.54m.		1	1	1		
10		161.54	166.12	Core is green with peach-filled fracs and selvages. K-spar grains are peach in color, combined with chl to give distinct color. Diss aspy present from 161.54 - 164.02m. Diss py present 164.02 - 164.50m.			2		2	3
10		166.12	172.21	Dark grey GND, chl and carb on frac faces. Diss aspy from 167.64 - 169.16m. Very few veins. Those present are small (0.2cm or less). Po makes its first major appearance @ 171.30m.			1		1	
10		172.21	173.48	Intense clay alt'n has made core soft and brittle. Fragments of unaltered GND can be seen within. Fractures filled with carb. Contact with unaltered GND at 30° to CA. Diss aspy is present.				3	1	
10		173.48	179.83	Light grey, med gr GND. Fractures contain ser and carb alt'n. Fractures @ 20° and 50°. Very few veins found in this section. Those that do occur are 0.2cm or less.		1			2	
10		179.83	182.88	GND is finer grained with less carb alt'n. Fracture surfaces show chl alt'n and euhedral aspy crystals. Core is highly fractured and broken. 40% gravel size, 60% > 5cm.			2			
10		182.88	195.37	Fine gr unaltered GND. Dark grey in color with an increase in bt and hbl. Fractures show chl alt'n, carb limited to a few selvages. Core is less broken. Few veins, but sulphide veinlets are common. Po is dominant sulphide at these depths, with minor cpy also present. Aspy can also be found in trace quantities.			1			
	EOH									

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B380570	STANDARD 4D		0.440	4D		VA05060563	
5	1	0.2	1.0	40		0.2	q	2	0				0.1									B380571	149.35	150.88	0.168			VA05058631	1.53
4	1	0.2	0.8	40		0.2	chl	3	0				0.1									B380572	150.88	151.49	0.104			VA05058631	0.61
2	1	2.0	2.5	40		0.2	q	3	0				3.0									B380573	151.49	152.40	0.200			VA05058631	0.91
4	1	0.2	0.8	40		0.2	q	3	0				3.0									B380574	152.40	153.92	0.149			VA05058631	1.52
4	6	0.5	2.0	50						100.0								30.0				B380575	153.92	155.45	0.142			VA05060563	1.53
4	1	0.5	1.1	40		1.0	k	4	0	5.0			3.0																
																						B380576	BLANK		<0.005			VA05060563	
8	1	1.0	2.4	40		2.0	k	4	0	0.1			5.0									B380577	155.45	156.97	0.068			VA05060563	1.52
3	1	0.5	0.9	40		0.2	k	4	0				1.0									B380578	156.97	157.74	0.066			VA05060563	0.77
1	1	0.2	0.2	40									0.1									B380579	157.74	158.50	0.034			VA05060563	0.76
2	1	0.2	0.2	40		0.2	q	2	0				0.1									B380580	158.50	160.02	0.049			VA05058631	1.52
																						B380581	160.02	161.54	0.046			VA05058631	1.52
																						B380582	160.02	161.54	0.060	DUP		VA05058631	1.52
4	1	0.2	0.8	40		0.2	q	3	0				0.1									B380583	161.54	163.07	0.090			VA05058631	1.53
4	1	0.5	1.1	40		0.2	k	4	0				0.1									B380584	163.07	164.59	0.056			VA05058631	1.52
7	1	0.2	1.4	40		0.2	q/k	3	0				3.0									B380585	164.59	166.12	0.059			VA05058631	1.53
2	6	0.2	0.4	40									100.0									B380586	166.12	167.64	0.046			VA05058631	1.52
3	1	1.0	1.4	40		1.0	q	3	0				1.0									B380587	167.64	169.16	0.054			VA05060563	1.52
1	1	1.0	1.0	40		0.2	chl	4	0				1.0									B380588	169.16	170.69	0.093			VA05060563	1.53
1	1	1.0	1.0	40		0.2	chl	4	0				1.0									B380589	169.16	170.69	0.077	PD/CA		VA05060563	1.53
																						B380590	STANDARD 4D		0.442	4D		VA05060563	
3	1	2.0	2.4	40	170	0.2	chl	4	0		3.0		1.0									B380591	170.69	172.21	0.072		po found in 170 deg vein	VA05060563	1.52
6	6	0.5	1.5	50									100.0									B380592	172.21	173.48	0.086			VA05060563	1.27
11	1	0.2	2.2	40		0.2	q	2	0				1.0									B380593	173.48	175.26	0.078			VA05060563	1.78
2	1	0.2	0.4	40		0.2	q	2	0				1.0									B380594	175.26	176.78	0.051			VA05060563	1.52
2	4	0.2	0.4	40																		B380595	176.79	178.31	0.036			VA05060563	1.52
																						B380596	BLANK		<0.005			VA05060563	
3	1	1.0	2.2	40		0.2	q	3	0				1.0									B380597	178.31	179.83	0.028			VA05060563	1.52
3	1	0.2	0.6	40		0.2	chl	2	0				1.0									B380598	179.83	181.36	0.092			VA05060563	1.53
2	6	0.2	0.4	40									100.0																
3	1	1.0	1.4	40		0.2	chl	3	0				3.0									B380599	181.36	182.88	0.043			VA05060563	1.52
2	1	0.2	0.4	40		0.2	q	3	0				0.1									B380600	182.88	184.40	0.029			VA05060563	1.52
3	6	0.2	6.0	40		0.2	q	3	0				100.0									B380601	184.40	185.93	0.028			VA05060563	1.53
3	6	0.2	6.0	40		0.2	q	3	0				100.0									B380602	184.40	185.93	0.054	DUP		VA05060563	1.53
2	6	0.2	0.4	40		0.2	q	3	0				100.0									B380603	185.93	187.45	0.047			VA05060563	1.52
2	1	0.2	0.2	40									0.1									B380604	187.45	188.98	0.019			VA05060563	1.53
3	1	0.2	0.6	40		0.2	q	4	0	1.0												B380605	188.98	190.50	0.028			VA05060563	1.52
3	1	0.5	0.9	40		0.2	q	2	0	15.0	5.0											B380606	190.50	192.02	0.019			VA05060563	1.52
5	1	0.2	1.0	40		0.2	q	2	0		10.0	1.0	0.1									B380607	192.02	193.55	0.027			VA05058631	1.53
3	1	0.2	0.6	40		0.5	q	3	0		3.0											B380608	193.55	195.37	0.026			VA05058631	1.52
3	1	0.2	0.6	40		0.5	q	3	0		3.0											B380609	193.55	195.37	0.028	PD/CA		VA05058631	1.52
																						B380610	STANDARD 2B		3.000	2B		VA05058631	
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-289C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 961m

BEARING: 000 | DIP: -50°

DATE STARTED: 22-Jun-05 | DATE COMPLETED: 24-Jun-05

LOGGED BY: Terry Croteau June 26-July 1, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459560 NORTHING: 7099246

COORD SYSTEM: NAD 83: EASTING: 459442 NORTHING: 7099434

NAD 27 (CORRECTED for historic grid): EASTING: 459530 NORTHING: 7099256

SECTION LINE(historic grid): 459530

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 7.01m

Deviation:

Casing: 7.01m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	7.01	Casing/OVB
7.01	53.64	MSED
53.64	207.26	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B381684-B381716

Requisition #: MASP448STRGOL.05Q Date Shipped:

Lab Record #: VA05055279 Date Received: 8-Jul-05

Sample Sequence: B381717-B381878

Requisition #: MASP448STRGOL.05Q Date Shipped:

Lab Record #: VA05058632 & VA05060567 Date Received: 15-Jul-05 & 21-Jul-05

Special Note: Samples divided between lab records - most of hole between these two.

Duplicates:	381702; 381722; 381742; 381762; 381782; 381802; 381822; 381842; 381862
Preparation Duplicate/ Check Assay:	381689; 381709; 381729; 381749; 381769; 381789; 381809; 381829; 381849; 381869
Standards:	381690 (3C); 381710 (1A); 381730 (5E); 381750 (3C); 381770 (7G); 381790 (1A); 381810 (7G); 381830 (3C); 381850 (4D); 381870 (2B)
Blanks:	381696; 381716; 381736; 381756; 381776; 381796; 381816; 381836; 381856; 381876

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	340.7	61.0	006.7	007.7
150.0	345.1	61.2	011.1	012.1
207.26	346.0	61.4	012.0	013.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE	of 10
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 7.01			Casing/Overburden						
80	7.01 - 53.61			MSED: Variable composition/textures and mineralogy						
80		7.01	9.14	MSED rusty brown in color; Foliation at 30° TCA; Core very coherent and recovery is good: At 9.01m clayey gouge contains qtz eyes and MSED frags	2					
80		9.14	15.24	MSED core is broken into angular frags less than 8cm in diam; Poor recovery ~30%; At 11.69m, 5cm quartz vein at 50° TCA contains 5% aspy in fractures; Aspy appears to have weathered out of the remaining fractures.	1					
80		15.24	15.69	45cm clay gouge; Brown rusty color at 40° TCA; Contains qtz eyes and MSED frags; Adjacent rock is highly fractured and friable; Gouge is soft but coherent	3			4		
80		15.69	16.09	Broken rusty colored MSED; Limonite staining on fractures; Pieces <10cm	1					
80		16.09	17.89	MSED limonite staining on fracture; Foliation at 40°.	1					
80		17.89	20.12	Core is broken; Gravel size frags pervasive limonite and on fractures; At 19.43m, 38 cm gouge at 80° TCA, qtz eyes and MSED frags present	3					
80		20.12	20.71	MSED; Increase in competency and rec; Limonite stain on fractures only; Foliation at 45° TCA	1					
80		20.71	21.34	Core is composed of rounded MSED frags within a black matrix; Soft, altered to clays; Possible FAULT; No visible slip direction; Core crumbles if touched.	1					
80		21.34	23.62	MSED; Good recovery; Foliation at 40° TCA; Minor pervasive limonite; Limonite on fractures dominantly	2					
80		23.62	24.38	Core becomes fractured, recovery decreases; Broken fragments < 15cm; Foliation continues at 40° TCA	1					
80		24.38	27.80	Core regains competence; Good recovery; Limonite on fractures; Foliation still at 40° TCA; At 26.89m 15cm GND dyke at 40° TCA; At 27.23m 8cm GND dyke at 40° TCA						
80		27.80	28.79	MSED broken into gravel size fragments; Rounded; Limonite is pervasive; Quartz fragments indicate possible veins; At 28.1m, 8cm clayey gouge, contains quartz eyes.	3					
80		28.79	31.82	Core again competent with good recovery; Limonite on fracture faces; Foliation at 40° TCA; Quartz becoming interbedded in the MSED at 40°.						
80		31.82	32.25	Core is broken into gravel sized frags; Heavy limonite staining on fractures	2					
80		32.25	33.33	MSED: Competent fractures at 40° and 130° TCA; 130° cross cuts foliation running at 40°; minor staining on fractures faces.	1					
80		33.33	33.87	52cm gouge unit at 30° TCA crosscutting the foliation; Gouge contains qtz eyes and MSED frags; Minor limonite staining.	1					
80		33.87	40.24	Core becomes dark green-black MSED; Foliation is harder to distinguish, where visible it is at 40° TCA, but changes to 5° TCA and becomes crenulated at 36.69m; Foliation returns to 40° TCA at 37.23m; Fractures continue at 40° and 130° TCA.	1					
80		40.24	44.00	Core is fragmented with heavy limonite staining on fractures; Foliation at 40° TCA; At 43.89m 4cm GND dyke flanked by 1cm veins at 40° TCA						
80		44.00	44.85	Core is more competent; Limonite and sericite on fractures; Foliation at 40° TCA						
80		44.85	48.97	Core is again fragmented; Foliation is at 10° TCA; Minor limonite staining on fractures; 47.74 - 48.77m recovery is 10%						
80		48.97	53.49	MSED: Core is fractures and broken with sericite alteration and pervasive limonite foliation at 85° TCA; At 48.97m a 10cm clay gouge at 85° TCA contains qtz eyes and MSED frags; At 50.71m a 10cm clay gouge at 85° TCA contains qtz eyes and GND frags						
80		53.49	53.64	MSED/GND ctc; MSED is folded with qtz eyes, slickenslides present on fractures and contact; At 53.56m a 5cm black gouge composed of MSED frags, qtz eyes and GND frags						
10	53.64 - 207.26			GND: Fine to med grained; The majority of the veinage occurs after 67.2m						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
0																						B381684	7.01	7.62	0.018			VA05055279	0.61
0																						B381685	7.62	9.14	0.052			VA05055279	1.52
0																						B381686	9.14	10.67	0.021			VA05055279	1.53
1	1	5.0	5.0	30		0.0							2.0					90.0				B381687	10.67	12.19	0.019			VA05055279	1.52
0																						B381688	12.19	13.72	0.005			VA05055279	1.53
0																						B381689	12.19	13.72	0.005	PD/CA		VA05055279	1.53
																						B381690	STANDARD 3C		0.094	3C		VA05055279	
0																						B381691	13.72	15.24	0.006			VA05055279	1.52
0																						B381692	15.24	15.69	0.053			VA05055279	0.45
0																						B381693	15.69	16.76	0.151			VA05055279	1.07
2	1	7.0	9.0	40		0.0					1.0							100				B381694	16.76	18.29	1.685			VA05055279	1.53
0																						B381695	18.29	19.81	0.053			VA05055279	1.52
																						B381696	BLANK		<0.005			VA05055279	
0																						B381697	19.81	20.71	0.064			VA05055279	0.9
																						B381698	20.71	21.34	0.051			VA05055279	0.63
3	1	7.2	7.0	50		0.0																B381699	21.34	22.86	0.715			VA05055279	1.52
2	1	0.2	0.9	50		0.0				1												B381700	22.86	24.38	0.254			VA05055279	1.52
1	1	2.0	2.0	60		0.0																B381701	24.38	25.91	0.349			VA05055279	1.53
1	1	2.0	2.0	60		0.0																B381702	24.38	25.91	0.185	DUP		VA05055279	1.53
2	1	0.2	0.4	50		0.0																B381703	25.91	27.43	0.060			VA05055279	1.52
1	1																					B381704	27.43	28.96	0.019			VA05055279	1.53
1	1	0.5	0.5	45		0.0																B381705	28.96	30.48	0.005			VA05055279	1.52
0																						B381706	30.48	32.00	0.084			VA05055279	1.52
1	6	0.2	0.2	40						100												B381707	32.00	33.33	0.009			VA05055279	1.33
0																						B381708	33.33	33.87	<0.005			VA05055279	0.54
0																						B381709	33.33	33.87	<0.005	PD/CA		VA05055279	0.54
																						B381710	STANDARD 1A		0.931	1A		VA05055279	
0																						B381711	33.87	35.05	0.006			VA05055279	1.18
2	1	4.0	8.0	50	20	0.0							1.0									B381712	35.05	36.58	3.600			VA05055279	1.53
2	1	1.5	2.0	20		0.0																B381713	36.58	38.10	1.365			VA05055279	1.52
1	1	2.5	2.5	45		0.0																B381714	38.10	39.62	0.024			VA05055279	1.52
1	1	8.0	8.0	40		0.0				0.1			1.0									B381715	39.62	41.15	0.040			VA05055279	1.53
0																						B381716	BLANK		<0.005			VA05055279	
																						B381717	41.15	42.67	0.082			VA05058632	1.52
3	1	1.0	3.0	40		0.0																B381718	42.67	44.20	0.034			VA05058632	1.53
1	1	7.0	7.0	40		0.0																B381719	44.20	45.72	0.278			VA05058632	1.52
0																						B381720	45.72	47.24	0.098			VA05058632	1.52
0																						B381721	47.24	48.77	0.035			VA05058632	1.53
0																						B381722	47.24	48.77	1.845	DUP		VA05058632	1.53
0																						B381723	48.77	50.29	0.051			VA05058632	1.52
																						B381724	50.29	51.82	0.252			VA05058632	1.53
																						B381725	51.82	53.34	0.508			VA05060567	1.52
1	1	0.5	0.5	45		1.0	q	3	0													B381726	53.34	53.64	0.064			VA05060567	0.3

DRILL HOLE # : DG05-289C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		53.64	60.56	Moderately broken altered GND; Hematite is pervasive and on fractures; Fractures occur at 45° and 80° TCA; Core is highly fractured and broken; Minor clay alteration on fractures; At 59.44m sugary texture intersected by 9cm qtz veins	2			1		
10		60.56	63.79	Core is still fractured and broken; but pervasive limonite is reduced as well; Less on fractures; Also, very little clay alteration; At 61.3m to 62m minor clay alteration on fractures	1					
10		63.79	66.56	GND is grey in color and altered to sericite; Texture is soft but coherent; Core is permeable; Recovery is poor; Fracture angles observed by texture.	2	2		1		
10		66.56	88.92	Unaltered GND; Pervasive Limonite is absent, found only on fractures; Fractures at 40° and 110° TCA; Carbonate also found on fractures; Recovery is good; At 73.15m minor sericite on fractures; At 76.95m, 7cm qtz vein at 60° TCA; At 77.03m, 6cm qtz veins at 60° TCA; At 88.29m, a 6cm qtz vein at 30° TCA; At 88.89m, 8cm qtz vein at 30° TCA; Veining increases in size after 75.65m as well as in frequency; Sulphides begin to appear in veins; The majority is aspy with minor py; Most veins contain only trace amounts of either sulphide.	1					
10		88.92	92.96	Unaltered GND; Limonite no longer present in any form; GND is dark grey with increased veinage.		1				
10		92.96	93.76	GND is greenish grey; Mafics almost totally absent; Chl alteration dominant; Possibly a large selvage; At 92.46m, 2cm clay gouge at 40° TCA			2			
10		93.76	96.01	Unaltered GND; Fractures at 60° and 120°; Reduction in number and frequency of veins; GND is still dark grey.						
10		96.01	96.61	Core is light grey to green; Sericite and chlorite alteration present; Metased xenolith at 96.13 to 96.50m; 4cm grey gouge at 45° TCA, 2cm rusty stain of hematite.		1	2	1		
10		96.61	103.63	Unaltered GND; Fractures at 30° and 100° TCA; Carbonate present on most veins; Disseminated pyrite found at 102.11m; Possible fine grained VG(?)						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorolite	biotite	other		From	To					
1	1	0.5																				B381727	53.64	54.86	0.076			VA05060567	1.22
1	1	0.2	0.2	30									0.1									B381728	54.86	56.39	0.081			VA05060567	1.53
1	1	0.2	0.2	30									0.1									B381729	54.86	56.39	0.098	PD/CA		VA05060567	1.53
																						B381730	STANDARD 5E		1.415	5E		VA05060567	
0																						B381731	56.39	57.91	0.095			VA05060567	1.52
3	1	2.0	4.2	45	10	0.0							0.1									B381732	57.91	59.44	0.200			VA05060567	1.53
1	1	10.0	10.0	45		0.0																B381733	59.44	59.62	0.073			VA05060567	0.18
0																						B381734	59.62	60.96	0.041			VA05060567	1.34
																						B381735	60.96	62.48	1.085			VA05060567	1.52
1	1	1.5	5.0										0.1									B381736	BLANK		<0.005			VA05060567	
																						B381737	62.48	64.01	2.150			VA05060567	1.53
1	1	2.0	2.0																			B381738	64.01	65.53	1.775			VA05060567	1.52
2	1	0.2	0.2	45		0.0																B381739	65.53	67.06	0.025			VA05060567	1.53
1	1	1.5	1.5	30		0.0							1.0									B381740	67.06	68.58	0.084			VA05060567	1.52
2	1	2.0	4.0	20		0.0							1.0									B381741	68.58	70.10	0.054			VA05058632	1.52
2	1	2.0	4.0	20		0.0							1.0									B381742	68.58	70.10	0.342	DUP		VA05058632	1.52
3	1	0.5	0.9	40		0.0					1.0											B381743	70.10	71.63	0.010			VA05058632	1.53
2	1	0.5	0.7	40		0.0																B381744	71.63	73.15	0.047			VA05058632	1.52
1	6	0.2	0.2	15									100					60.0	10			B381745	73.15	74.68	0.075			VA05058632	1.53
3	1	1.0	2.0	35		0.0				2												B381746	74.68	75.65	0.061			VA05058632	0.97
3	1	3.0	8.0	35		0.0				2												B381747	75.65	76.20	0.204			VA05058632	0.55
3	1	1.2	2.0	30		0.0							0.1									B381748	76.20	77.72	0.070		Euhedral aspy on fract surf	VA05058632	1.52
3	1	1.2	2.0	30		0.0							0.1									B381749	76.20	77.72	0.065	PD/CA		VA05058632	1.52
																						B381750	STANDARD 3C		0.094	3C		VA05058632	
2	1	0.2	0.4	40		0.0					0.1											B381751	77.72	79.25	0.009			VA05058632	1.53
4	0	0.5	1.1	40		1.0	chl	3	0				0.1									B381752	79.25	80.77	0.070			VA05058632	1.52
3	1	0.2	0.6	35							0.1		0.1									B381753	80.77	82.30	0.100			VA05058632	1.53
4	1	1.0	1.5	40							0.1											B381754	82.30	83.82	0.148			VA05058632	1.52
5	1	1.5	4.0			0.2	q	3	0				1.0									B381755	83.82	85.34	0.102			VA05058632	1.52
																						B381756	BLANK		<0.005			VA05058632	
2	1	1.0	1.2	40																		B381757	85.34	86.87	0.073			VA05058632	1.53
3	1	0.2	0.6	40	10	0.2	q/chl	3	0				5.0									B381758	86.87	87.89	0.098			VA05058632	1.02
3	1	9.0	17.0	40		1.0	q/chl	3	0				3.0									B381759	87.89	88.49	1.210			VA05058632	0.6
4	1	3.0	5.0	40							0.1											B381760	88.49	88.92	0.046			VA05058632	0.43
4	1	2.0	5.0	50		2.0	chl	2	0	0.1	0.1											B381761	88.92	91.44	0.081			VA05058632	1.52
4	1	2.0	5.0	50		2.0	chl	2	0	0.1	0.1											B381762	88.92	91.44	0.066	DUP		VA05058632	1.52
8	1	5.0	13.0	40		1.0	q	3	0		0.1		3.0									B381763	91.44	92.96	0.154			VA05058632	1.52
4	1	6.0	30.0			0.0							5.0									B381764	92.96	93.76	0.547			VA05060567	0.8
1	1	1.5	1.5	35		0.0				1			1.0									B381765	93.76	94.48	0.049			VA05060567	0.72
4	1	1.0	3.0	35		0.0							1.0									B381766	94.48	96.01	0.078			VA05060567	1.53
0																						B381767	96.01	96.61	0.165			VA05060567	0.6
2	1	1.0	1.5	40	10	0.0					0.1		0.1									B381768	96.61	97.54	0.248			VA05060567	0.93
2	1	1.0	1.5	40	10	0.0					0.1		0.1									B381769	96.61	97.54	0.236	PD/CA		VA05060567	0.93
																						B381770	STANDARD 7G		4.340	7G		VA05060567	
1	1	0.2	0.2	35		0.0							15									B381771	97.54	99.06	0.056			VA05060567	1.52
2	1	0.2	1.2	5	35	0.0				0.1			1.0									B381772	99.06	100.58	0.042			VA05060567	1.52
2	1	1.0	1.2	35		1.0	chl	3	0				3.0									B381773	100.58	102.11	0.136			VA05060567	1.53
1	1	0.2	0.2	35		0.0				5	15.0											B381774	102.11	103.63	0.169			VA05058632	1.52

DRILL LOG LEGEND - P1	DATE: June 22 - 24, 2005	PAGE 5 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		103.63	111.25	Unaltered GND; Good recovery; Fractures are at 35° and 110° TCA; Color is lighter grey than previous; Sulphides increase in concentration with po and cpy as dominant sulphides; Diss py and aspy still present on fractures; Fine grained, difficult to distinguish with hand lens; May be fine grained gold (?) present; The fractures containing sulphides also show slickenslides beneath.						
10		111.25	116.71	Unaltered GND; Light grey, becoming med grained; Fractures at 50° and 80° TCA; Po and aspy dominate vein sulphides; Trace disseminated aspy still present; At 113.38m 4cm gouge at 85° TCA; At 117.05m aspy showing slickenslides.						
10		116.71	120.40	GND is light green color and scratches easily; core is highly fractures and broken; Fractures occur at 50°, 80°, and 110° TCA; Pieces range from gravel size to >10cm; 50° fractures frequently contain slicks, but no mineralization.		1	1			
10		120.40	128.02	Unaltered GND, grey, fine grained; There is less mineralization present in the veins, but aspy is now present disseminated in the selvages.						
10		128.02	130.66	Unaltered GND; Decrease in veins and mineralization. Good recovery; Aspy found on slickenslides on fracture surfaces; Fractures at 30°, 60° and 120°.						
10		130.66	134.11	Chlorite alteration as well as sericite alteration on fractures; The number of veins increases as does mineralization; Core is broken with most fractures random; recovery is less than previous interval.		1	1			
10		134.11	135.36	Core is green, more chlorite alteration and an increase in the size of veins; This is also the start of a 10.32m zone of intense veining, alteration and mineralization at 135.36m		1	2			
10		135.36	135.64	28cm qtz vein; Total length may be greater as it was found at the end of run; Contact at 20° TCA; Fractures are filled with pyrite ~ 20%		2	3			
10		135.64	136.36	32cm qtz vein at 30° TCA, fractures filled with massive aspy; Selvage contains diss disseminated py						
10		136.36	137.86	Chlorite alteration is more intense; Core is highly fractured with clay in fractures; Quartz veins also fractured; Aspy fills fractures between qtz and altered GND		1	3			
10		137.86	138.16	Massive sulphide vein at 10° TCA; Composed of Aspy 70% oxidized; In 30cm quartz vein at 30° TCA; Py in qtz vein fracture						
10		138.16	139.40	Intensely altered GND; core is soft but competent; Clay and chlorite alteration; Quartz eyes and GND frags present; Disseminated aspy throughout						
10		139.40	139.96	56+cm quartz vein; vein is broken at both ends, and in the middle, true length may be greater, angle cannot be determined; Fractures are filled with massive aspy; Trace VG (?)						
10		139.96	141.73	GND; Altered chlorite and sericite; recovery good; Light green color; Disseminated pyrite found throughout, and in fractures						
10		141.73	145.60	Core is darker green color; Highly fractured and broken; Pieces range from gravel size to 20cm; Fractures continue to be filled with sulphides: aspy and py.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

PAGE 6 of 10

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.5	3.0	45		1.0	chl	3	0	0.1	3.0		1.0									B381775	103.63	105.16	0.450			VA05058632	1.53
																						B381776	BLANK		<0.005			VA05058632	
3	1	2.0	5.0	25		1.0	q	3	0	0.1	1.0	0.1	1.0									B381777	105.16	105.76	0.702			VA05058632	0.6
0																						B381778	105.76	106.68	0.356			VA05058632	0.92
2	1	6.0	7.0	50		0.0					15.0	3.0				0.5						B381779	106.68	107.18	0.968		1mm vg found in split core in cpy	VA05058632	0.5
2	1	0.2	0.4	20		0.2	q	3	0				0.1									B381780	107.18	108.20	0.528			VA05058632	1.02
4	1	1.0	2.5	30		0.2	q	3	0	5	3.0		1.0									B381781	108.20	109.73	0.928			VA05060567	1.53
4	1	1.0	2.5	30		0.2	q	3	0	5	3.0		1.0									B381782	108.20	109.73	0.987	DUP		VA05060567	1.53
4	1	1.0	2.5	30		0.5	cb	3	0	3	5.0		1.0									B381783	109.73	111.25	0.074			VA05060567	1.52
1	1	3.0	3.0	40							1.0	0.1										B381784	111.25	112.78	0.112			VA05060567	1.53
1	1	2.0	1.0	60							3.0	1.5										B381785	112.78	114.00	0.212			VA05058632	1.22
5	1	2.0	9.0	55							50.0	0.1	5.0									B381786	114.00	114.80	1.915			VA05058632	0.8
2	1	1.0	1.5	55	10						1.0		0.1									B381787	114.80	115.87	0.129			VA05058632	1.07
2	1	0.2	0.4	55							0.1											B381788	115.87	117.35	0.513			VA05058632	1.48
2	1	0.2	0.4	55							0.1											B381789	115.87	117.35	0.139	PD/CA		VA05060567	1.48
																						B381790	STANDARD 1A		0.933	1A		VA05060567	
1	1	0.2	0.2	55									0.1									B381791	117.35	118.87	0.250			VA05060567	1.52
6	1	2.0	5.0	30		1.0	chl	3	0				5.0									B381792	118.87	120.40	0.221			VA05060567	1.53
2	1	2.0	2.5	30		1.0	q	3	0		0.1											B381793	120.40	121.92	0.081			VA05060567	1.52
2	1	1.0	1.5	30		3.0	chl	3	0		0.1		1.0									B381794	121.92	123.44	0.134			VA05058632	1.52
2	1	1.0	1.5	30		2.0	chl	3	0	1								10.0				B381795	123.44	124.97	0.225			VA05058632	1.53
																						B381796	BLANK		<0.005			VA05058632	
3	1	0.1	2.5	30		4.0	chl	3	0		1.0											B381797	124.97	126.49	0.090			VA05058632	1.52
4	1	1.5	3.0	30		3.0	chl	3	0				0.1									B381798	126.49	128.07	0.434			VA05060567	1.58
1	1	1.0	1.0	30		0.0				0.1												B381799	128.07	129.54	0.151			VA05060567	1.47
1	1	0.2	0.2	15																		B381800	129.54	130.66	0.120			VA05060567	1.12
0																						B381801	130.66	131.06	1.135			VA05060567	0.4
0																						B381802	130.66	131.06	0.451	DUP		VA05060567	0.4
																						B381803	131.06	132.59	4.770			VA05060567	1.53
2	1	1.0	1.5	30	165					1			1.0									B381804	132.59	134.11	0.469			VA05060567	1.52
4	1	6.0	9.5	15		5.0	chl	4	0	5			5.0									B381805	134.11	135.36	0.720			VA05060567	1.25
1	1	28.0	28.0	20						20						0.2						B381806	135.36	135.64	7.090		Tr vg found in split core	VA05060567	0.28
0																						B381807	135.64	136.04	2.590			VA05060567	0.4
1	1	32.0	32.0	30						1			10					60.0				B381808	136.04	136.36	14.250			VA05060567	0.32
1	1	32.0	32.0	30						1			10					60.0				B381809	136.04	136.36	16.050	PD/CA		VA05060567	0.32
																						B381810	STANDARD 7G		4.740	7G		VA05060567	
																						B381811	136.36	137.86	2.140			VA05060567	1.5
1	1	30.0	30.0	30		0.0				5			1									B381812	137.86	138.16	14.250			VA05060567	0.3
1	6	2.0	2.0	10		0.0							100					70.0											
0																						B381813	138.16	139.40	5.570			VA05060567	1.24
1	1	56.0	56.0							3			15			0.1						B381814	139.40	139.96	14.000		Trace VG	VA05058632	0.56
2	1	2.0	3.0	30		3.0	chl	3	0	3												B381815	139.96	141.17	0.977			VA05058632	1.21
																						B381816	BLANK		0.008			VA05058632	
0																						B381817	141.17	142.31	0.008			VA05058632	1.14
3	1	3.0	5.0	30		4.0	chl	4	0	0.1			10			0.1						B381818	142.31	143.26	1.805			VA05058632	0.95
4	1	7.0	9.0	150	60	2.0	chl	3	0	3			1.0					40.0				B381819	143.26	144.78	0.219			VA05060567	1.52
5	1	9.0	17.5	150	60	5.0	chl	3	0	10			3.0					40.0				B381820	144.78	145.60	1.210			VA05060567	0.82

DRILL HOLE # : DG05-289C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		145.60	147.82	GND shown significantly less alteration being present; Mostly as vein selvages; Mineralization is reduced and core is more competent; Recovery is very good.			1			
10		147.82	155.77	Slightly altered GND; Core is dark grey/green; Core is highly fractured and broken; Recovery is less than previous; Po returns in veins. @151.14m, clay gouge at 30° TCA; 2cm gouge is followed by a broken qtz vein in deformed GND; Fracture face shows pyrite with slickenslides; Small fault, core is too broken to get width.			1			
10		155.77	161.54	Core is again green with chlorite; It is competent with good recovery; Quartz and carbonate mottle the core; Quartz veins are deformed, broken and fractured; Carbonate fills fractures, as well as possible tension gashes; At 160.97m qtz crystals show foliation direction at 45° TCA; Possible shear; Sulphides are found bordering carbonate filled fractures and gashes; Slickenslides present on some fractures.			3			
10		161.54	162.04	FAULT ZONE: Deformation is most intense; Fault is composed of black clay filled with porphyroclasts and quartz eyes in S-fabric indicates sinistral movement; Contact at 45° TCA; Py in fractures; At 161.94m fault gouge, 10cm, w/ quartz eyes.				5		
10		162.04	166.12	GND is moderately alt'd, pale green color. Highly fractured and broken w/ most of the core being gravel-sized w/ 10% being up to 10cm. Chl & ser alt'n on fracs. Some fracs filled w/ py. Recovery is less.		2	2			
10		166.12	170.69	Core shows similar alt'n but is more competent. Gravel-sized pieces are almost absent, w/ 85% greater than 10cm.		2	2			
10		170.69	175.26	Core becomes fractured and broken to gravel size pieces. Clay alt'n on frac increases. Decrease in vn size and frags. Core is light grey in color, med gr, dissem po present.		1	1	2		
10		175.26	176.78	Core changes to white-green in color and becomes broken. Carbonate alt'n dominant. Carb also found on frac faces.			2		3	
10		176.78	177.23	Core is alt'd heavily to clay; soft but competent. Qtz eyes and GND frags present. @177.12m: 30° contact w/ possible small (~2cm) fault. Qtz appears to show 30° foliation, contact @ black clay w/ py filled frac.						
10		177.23	179.64	Ser and chl alt'n in the form of selvages only. Alt'n of frac srfc's is limited to minor carb ~30°.						
10		179.64	182.38	Return to dark grey, unalt'd GND. Core is still fractured and broken, but recovery has increased. Fracs normally @60°. Po returns in vns.						
10		182.38	183.14	Core is light green colour, w/ ser alt'n on frac. @182.62m: ~2cm gouge @ 45° to CA, filled w/ black clay and massive py. Slickensides present.		1	2			
10		183.14	184.40	Clay alt'n increased, especially on fracs. Core crumbles when handled.				3		
10		184.40	185.63	Light green color, increased competence and recovery. @185.20m: 2cm sulphide vn @50° to CA; contact between chl and ser alt'n. Ser fills frac around round xenoliths of chl alt'd GND. Looks like a conglomerate.		2	2			
10		185.63	186.72	Grey GND, frac & broken frac @60° and 140°, less chl and ser.			1			
10		186.72	190.80	GND is more competent, better recovery. Clay alt'n is higher and core can be easily broken. Soft but coherent. Fracs @50° and 110°. Core is light grey color.		1	1	3		
10		190.80	192.87	Core is broken into gravel-sized pieces (80%) and frags >7cm. Less recovery, core is dark grey.				1		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval					
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	4	0.5	1.0	70																		B381821	145.60	146.30	0.030			VA05060567	0.7
2	4	0.5	1.0	70																		B381822	145.60	146.30	0.025	DUP		VA05060567	0.7
2	1	1.0	1.2	30	175	0.2	q	3	0	1												B381823	146.30	147.82	0.103			VA05060567	1.52
1	1	0.2	0.2	30		0.2	q	3	0		0.1											B381824	147.82	149.35	0.066			VA05058632	1.53
1	1	0.2	0.2	30		0.2	q	3	0		0.1											B381825	149.35	150.88	0.062			VA05058632	1.53
2	1	2.0	2.5	30									15									B381826	150.88	152.40	0.432			VA05058632	1.52
2	1	1.0	2.0	30									1.0									B381827	152.40	153.92	0.077			VA05058632	1.52
1	1	1.0	1.0	30									0.1									B381828	153.92	155.45	0.045			VA05058632	1.53
1	1	1.0	1.0	30									0.1									B381829	153.92	155.45	0.046	PD/CA		VA05058632	1.53
																						B381830	STANDARD 3C		0.094	3C		VA05058632	
3	1	1.0	1.5	4	30		0.2	cb	3	0			0.1									B381831	155.45	156.97	0.243			VA05058632	1.52
3	1	1.5	4.0																			B381832	156.97	158.50	0.126			VA05060567	1.53
	4												1.0																
4	1												1.0									B381833	158.50	160.02	0.143		vns too deformed for measurement	VA05060567	1.52
2	1												1.0									B381834	160.02	161.54	0.394		same as above	VA05060567	1.52
0																						B381835	161.54	162.04	0.325			VA05058632	.0.5
																						B381836	BLANK		<0.005			VA05058632	
3	1																					B381837	162.04	163.07	2.190		vns are broken	VA05058632	1.03
3	1																					B381838	163.07	164.59	0.918		vns are broken	VA05058632	1.52
2	1	2.0	3.0	30		0.2	chl	3	0			0.1										B381839	164.59	166.12	0.138			VA05060567	1.53
2	1	1.0	1.2	30	10					0.1												B381840	166.12	167.64	1.390			VA05060567	1.52
0																						B381841	167.64	169.16	0.581			VA05060567	1.52
0																						B381842	167.64	169.16	0.847	DUP		VA05058632	1.52
2	1	1.0	1.0	30		0.2	qtz	0	0				1.0									B381843	169.16	170.69	0.276			VA05058632	1.53
1	1	1.0	1.0	30									0.1									B381844	170.69	172.21	0.107			VA05058632	1.52
1	1	1.0	1.0	30							1.0											B381845	172.21	173.74	0.265			VA05060567	1.53
4	1												1.0									B381846	173.74	175.26	0.644		vns are broken	VA05060567	1.52
2	1	1.5	1.7	30		4.0	chl	3	0	1			0.1									B381847	175.26	176.78	0.569			VA05060567	1.52
0																						B381848	176.78	177.23	0.196			VA05060567	0.45
0																						B381849	176.78	177.23	0.116	PD/CA		VA05060567	0.45
																						B381850	STANDARD 4D		0.443	4D		VA05060567	
4	1	0.2	0.8	50						0.1			0.1									B381851	177.23	178.31	0.120			VA05060567	1.08
2	1	0.5	1.0	30									0.1									B381852	178.31	179.83	0.301			VA05060567	1.52
2	1	0.5	0.7	30							0.1	0.1	0.1									B381853	179.83	181.36	0.123			VA05060567	1.53
2	1	0.2	0.4	30								0.1	0.1									B381854	181.36	182.38	0.697			VA05060567	1.02
0																						B381855	182.38	183.14	1.535			VA05060567	0.76
																						B381856	BLANK		<0.005			VA05060567	
2	1	0.2	0.4	85						1												B381857	183.14	184.40	0.136			VA05060567	1.26
3	1	0.2	0.6	50						0.1												B381858	184.40	185.13	0.431			VA05060567	0.73
3	6	0.2	0.6	45		0.0				100								30.0				B381859	185.13	185.63	4.680			VA05060567	0.5
1	1	0.2	0.2	50		0.0																B381860	185.63	186.72	0.557			VA05060567	1.09
1	1	1.0	1.0	40		0.0							0.1									B381861	186.72	187.45	0.844			VA05060567	0.73
1	1	1.0	1.0	40		0.0							0.1									B381862	186.72	187.45	4.950	DUP		VA05060567	0.73
1	1	1.0	1.0	40		0.0							0.1									B381863	187.45	188.98	0.470			VA05060567	1.53
2	1	0.5	0.7	70		0.0																B381864	188.98	190.50	0.360			VA05060567	1.52
2	1	0.2	0.4	75		0.2	cb	3	0	0.1												B381865	190.50	192.02	0.532			VA05060567	1.52

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE 9 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		192.87	198.12	Return to clay alt'n. Core is soft but coherent, better recovery. Frac angles are difficult to obtain due to alt'n on frac, but appear to be @55° and 110°.		1	1	3		
10		198.12	200.07	Core is still soft but coherent. Many fracs are filled w/ black clay @199.39m, ~30cm. Qtz eyes and frags present between clay layers. Possible winged porphyroblast. This may be a fault. GND is white-light grey.		1	1	4		
10		200.07	205.74	At 35° contact w/ white GND at 0.5cm carb vn. GND is grey to dark grey. Competence increased and good recovery. Alt'n is limited to minor chl on frac faces. Frac at 10° and 30°, med gr.						
10		205.74	207.26	GND becomes darker grey, finer-grained.						
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	2.0	2.4	60		0.2	cb	3	0		1.0											B381866	192.02	193.55	**2.240**			VA05060567	1.53
3	1	0.2	0.6	60		0.0							0.1									B381867	193.55	195.07	**1.035**			VA05058632	1.52
1	6	0.5	0.5	80		0.0							100					10.0											
1	1	0.2	0.2	60		0.0							0.1									B381868	195.07	196.60	**0.743**			VA05058632	1.53
1	1	0.2	0.2	60		0.0							0.1									B381869	195.07	196.60	**0.665**	PD/CA		VA05058632	1.53
																						B381870	STANDARD 2B		**3.010**	2B		VA05058632	
3	1	1.5	1.9	60		0.0																B381871	196.60	198.12	**2.150**			VA05058632	1.52
0																						B381872	198.12	199.69	**0.593**			VA05060567	1.57
1	4	0.5	0.5	35		0.0																B381873	199.69	201.17	**0.202**			VA05060567	1.48
3	1	1.0	1.4	60	80	0.0				0.1												B381874	201.17	202.69	**0.246**		2% moly in vns	VA05060567	1.52
2	1	0.5	0.7	60		0.0																B381875	202.69	204.22	**0.329**			VA05060567	1.53
																						B381876	BLANK		**<0.005**			VA05060567	
0																						B381877	204.22	205.74	**0.373**			VA05060567	1.52
0																						B381878	205.74	207.26	**0.319**			VA05060567	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-290C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 905m

BEARING: 180 | DIP: -50°

DATE STARTED: 23-Jun-05 | DATE COMPLETED: 26-Jun-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459109 NORTHING: 7099040

COORD SYSTEM: NAD 83: EASTING: 4598991 NORTHING: 7099224

NAD 27 (CORRECTED for historic grid): EASTING: 459079 NORTHING: 7099050

SECTION LINE(historic grid): 459079E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 4.57m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381927 - B382075 and B382080 - B382098

Requisition #: MASP448STRGOL.05Q | Date Shipped: 8-Jul-05

Lab Record #: VA05060235, VA05058633 (alternating) | Date Received: 21-Jul-05, 15-Jul-05

Sample Sequence: B382076 - B382079

Requisition #: MASP448STRGOL.05Q | Date Shipped: 8-Jul-05

Lab Record #: VA05060567 | Date Received: 21-Jul-05

Sample Sequence: BB382099 - B382156

Requisition #: MASP448STRGOL.05Q | Date Shipped: 10-Jul-05

Lab Record #: VA05060237, VA05058634 (alternating) | Date Received: 21-Jul-05, 15-Jul-05

Duplicates:	B381942, B381962, B381982, B382002, B382022, B382042, B382062, B382082, B382102, B382122, B382142
Preparation Duplicate/ Check Assay:	B381929, B381949, B381969, B381989, B382009, B382029, B382049, B382069, B382089, B382109, B382129, B382149
Standards:	B381930 (3C), B381950 (5E), B381970 (7G), B381990 (2B), B382010 (6F), B382030 (6F), B382050 (1A), B382070 (5E), B382090 (7G), B382110 (1A), B382130 (4D), B382150 (7G)
Blanks:	B381936, B381956, B381976, B381996, B382016, B382036, B382056, B382076, B382096, B382116, B382136, B382156

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	149.4	-51.4	175.4	176.4
125.0	146.4	-52.6	172.4	173.4
197.0	146.9	-53.2	172.9	173.9

FROM	TO	THOLOGY
4.57	4.75	Schistose Argillite
4.75	22.50	GND, varying degrees of alt'n
22.50	24.38	Sand/Gravel
24.38	29.96	GND, varying degrees of alt'n
29.96	29.14	Beach Sand
29.14	30.50	GND, varying degrees of alt'n
30.50	30.60	Variable Pebbles and Sand
30.60	32.00	GND, varying degrees of alt'n
32.00	32.30	Sand
32.30	196.60	GND, varying degrees of alt'n

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 1 of 16										
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd		Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered				Carbonate 0 = No Effervescence 5 = Strong Effervescence					
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)							
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
-1	0-4.57	0.00	4.57	Casing--No recovery (casing to 4.75m w/ recovery)..								
80	4.57-4.75	4.57	4.75	Schistose argillite. Fine laminations (meta-seds), denoted by layered micas-musc & bt.	0	0	1	0	0			
10	4.75-22.50	4.75	5.60	GND, relatively competent. Unalt'd btwn vnlets, covered w/ limonite-selvages up to 0.5cm wide. Broken on vnlets.	1	0	1	0	1			
10		5.60	15.00	Brown, crumbly, limonized GND. Lim is pervasive. whole rock appears oxidized; largest core pc is ~8cm long. Most <2cm in diameter. Reduced to coarse sand @ 7.0m, for 20cm. Ave recovery for this section is 33.8%.	4	1	1	3	2			
10		15.00	20.15	More competent GND infused w/ zoned k-spar/qtz vns. These k-spar/qtz vns' zonation is highlighted by 1-2mm wide layers of oxidized hematite, producing a rosy red/deep orange color, which appears to pervade the whole rock. Also throughout is minor chlorite alt'n and silicification. From 15.86m-19.81m: vns are not clearly visible (only few small ones), but rock is still extensively hem & lim stained and alt'd. Slickensides on 45° face w/in clay alt'd section, 20cm wide at 17.3m.	4	2	3	2	2			
10		20.15	22.20	Highly alt'd GND; 90% GND texture is erased to fine-gr, v. colourful rock. Colors due to chl, lim, clay weathering (white-yellow), ox'd sulphides (black).	4	3	3	4	1			
10		22.20	22.50	Bleached, soft GND. Texture normal (visible grains), but more crumbly and broken up.	2	0	0	2	0			
1	22.50-24.38	22.50	24.38	Highly alt'd, broken up to crumbly to coarse sand-sized pc's. Hematite staining also continues, through 40% of section. Lim staining through all, and covering frac srfc's. Pocket of clean 'beach' sand at 22.86m-23.0m, hypotheses to follow @ 29.14m.	4	0	2	1	0			
10	24.38-28.96	24.38	28.96	Drastic change in lithological alt'n to pale bluish white, crumbly, clay & chl alt'd GND. @26.8m: sulphide vn is 80% ox'd py, 20% aspy in slickenside form.	0	4	3	3	0			
1	28.96-29.14	28.96	29.14	Light to med brown sand, size 1mm grains of bt, qtz, feldsp. Well-sorted beach sand. Origin unknown. Ideas: (1) Frac infill; (2)Ground up GND then washed w/ water (but no evidence of frac or fault); (3)Contamination from above in hole (but no record of problem from drill). Three more zones of washed sand/gravel in hole as well, w/in 15m zone.	1	0	0	0	0			
10	29.14-30.50	29.14	30.50	Clay/chl alt'd GND as previous to sand.								
1	30.50-30.60	30.50	30.60	Subangular to subrounded pebbles-cobbles of metaseds (50%) and pure qtz (30%). 20% silty sand, med brown.								
10	30.60-32.00	30.60	32.00	Clay/chl'd GND as before pebbles	0	4	3	4	0			
1	32.00-32.30	32.00	32.30	Light to med brown sand, well-sorted except first 5cm has dark grey clay (30%). Parts up to 10cm long were core-shaped but not competent.								
10	32.30-196.90	32.30	34.00	Sericitized GND, orig texture 80% erased. Evidence of shear; slickensides shown on frac faces & w/in soft, alt'd zones; shown in feldspars (plagioclase) and sericite.	0	4	1	2	0			

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, gc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	2.0	2.0																			B381927	4.57	4.75	0.006		qtz pc's	VA05060235	0.18
1	6	0.3	0.3	20		0				20			60.0					4.0	0.0			B381928	4.75	5.60	0.038			VA05060235	0.85
1	6	0.3	0.3	20		0				20			60.0					4.0	0.0			B381929	4.75	5.60	0.036	PD/CA		VA05060235	0.85
																						B381930	STANDARD 3C		0.094	3C		VA05060235	
0																						B381931	5.60	6.10	0.022			VA05060235	0.50
0																						B381932	6.10	7.62	0.042			VA05060235	1.52
0																						B381933	7.62	9.14	0.012			VA05060235	1.52
0																						B381934	9.14	10.67	0.018			VA05060235	1.53
2	1	0.5	1.0	65		4	qtz	2	3													B381935	10.67	12.19	0.037			VA05060235	1.52
							chl	1														B381936	BLANK		<0.005			VA05060235	
0																						B381937	12.19	13.72	0.023			VA05060235	1.53
2	1	0.4	0.7			100	s/chl	4,1	3					0.1								B381938	13.72	15.00	0.021		crumbly pc's	VA05060235	1.28
							q/cb	1,3																					
3	2	1.0	2.0	10	40	10	q/k	2	1													B381939	15.00	15.85	0.020			VA05060235	0.85
							chl	1																					
1	1	0.7	0.7	45		5	q/chl	1,2	3					2.0															
																						B381940	15.85	16.76	0.027			VA05060235	0.91
	6	0.3	0.3	30		1.5	q/cb	2	3	60								5.0				B381941	16.76	18.29	0.066			VA05060235	1.53
1	6	0.3	0.3	30		1.5	q/cb	2	3	60								5.0				B381942	16.76	18.29	0.071	DUP		VA05060235	1.53
1	6	0.4	0.4	15		3	qtz	3	4	60								5.0				B381943	18.29	19.81	0.030			VA05060235	1.52
1	1	0.6	0.6	60		10	q/cb	2	2	15								4.0											
0																						B381944	19.81	20.15	0.010			VA05060235	0.34
2	1	0.4	0.8	20		0				15								5.0				B381945	20.15	21.34	0.071			VA05060235	1.19
0																						B381946	21.34	22.20	0.115			VA05060235	0.86
1	1	0.3	0.3	20		10	qtz	2	3	5								5.0				B381947	22.20	22.50	0.017		loose pebbles	VA05060235	0.30
0																						B381948	22.50	23.70	0.218			VA05060235	1.20
0																						B381949	22.50	23.70	0.250	PD/CA		VA05058633	1.20
																						B381950	STANDARD 5E		1.475	5E		VA05058633	
0																						B381951	23.70	24.38	0.025			VA05058633	0.68
0																						B381952	24.38	25.91	0.024			VA05058633	1.53
1	6	0.2	0.2	40		2	chl/s	3,4	0	80			10.0					5.0	0.0			B381953	25.91	27.43	0.038			VA05058633	1.52
1	2	0.5	0.5			15	chl/s	3,4	0	0																	crumbly pc's		
2	1	0.5	1.0	45		1	q/s	2,3	0	5			10.0					5.0	0.0			B381954	27.43	28.96	0.032			VA05058633	1.53
							chl	3																					
0																						B381955	28.96	29.14	0.039			VA05058633	0.18
																						B381956	BLANK		<0.005			VA05058633	
2	1	0.5	1.0			100	chl/s	3	0	5								5.0				B381957	29.14	30.50	0.034			VA05058633	1.36
0																						B381958	30.50	30.60	0.029			VA05058633	0.10
2	6	0.5	0.7	60		5	chl/s	4,5	0	100								5.0				B381959	30.60	32.00	0.160			VA05058633	1.40
0																						B381960	32.00	32.30	0.193			VA05058633	0.30
1	6	0.4	0.4	20		10	chl/s	1,4	0	100								5.0				B381961	32.30	33.53	0.025			VA05060235	1.23
2	2	0.5	1.0	40		1	k/chl	2,1		100								5.0											
							s	4	0																					
1	6	0.4	0.4	20		10	chl/s	1,4	0	100								5.0				B381962	32.30	33.53	0.015	DUP		VA05060235	
2	2	0.5	1.0	40		1	k/chl	2,1		100								5.0											
0																						B381963	33.53	34.00	0.038			VA05060235	0.47

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		34.00	37.20	Alt'd GND; less sericite, chl & clay; more silicified; appears heated to aphanitic texture w/ oxidized sulphides. Overall color is dark brownish grey. Vnlets all rearranged, convoluted directions, lim. Dark grey sand makes up 5% of first sample (appears as first 5cm of section, little bit under core in box).	3	1	0	1	0	
10		37.20	39.88	Minor alt'd GND w/ small sulphide vns at random orientations, bent and sheared. Mostly ox'd sulphides in vns w/ milky qtz & feldspar (k-spar).	1	1	1	0	0	
10		39.88	43.35	Minor alt'n grading to mod alt'd GND, mostly chloritization. GND texture preserved and core remains relatively competent. Slickensides on vn faces shown in k-spar & ox'd py.	1	1	3	0	0	
10		43.35	52.54	Sericitized & chloritized, soft GND. Alt'n is pervasive so rock is crumbly: pale greenish grey to white. ~2 sulphide vns per metre on frac faces, usually at 20-30° to CA. Ox'd py and ser form slickensides, vns rearranged to random orientations.	0	4	3	3	0	
10		52.54	57.74	Original GND texture reappears and selvages are more clearly visible around vns. Rock is less sheared as well; less movement indicated in vns.	0	3	2	2	1	
10		57.74	59.07	Highly alt'd GND; wide selvages around sulphide and sulphide/qtz vns make rock crumbly, especially at vns. Minor slickensides on these faces.	1	4	3	2	0	
10		59.07	65.40	Highly-mod alt'd GND. Orig texture preserved btwn vns' selvages. 75% alt'd, v. broken up & crumbly. Slickensides appear @ 63.5m, none previous.	0	3	2	1	1	
10		65.40	66.17	Three large sulphide vns (3cm, 1cm, & 1cm wide) surrounded by extremely alt'd but competent core. GND texture completely erased.	1	4	3	2	2	
10		66.17	73.68	Mod alt'd GND. Orig texture preserved btwn vns' selvages. More competent and recovery is good (>80%). From 66.17m-67.06m: core is striped w/ bands of silicified old qtz vns. V. minor (<2%) ox'd py associated, not used in vn count. Vnlets of carb shift sulphide vns dextrally if sulph vn is to 60°.	0	3	2	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	6	0.8	2.0	50	25	2	k/chl	2,1		100								5.0				B381964	34.00	35.05	0.538			VA05060235	1.05
							s	3																					
4	6	0.5	2.0	10		0.5	chl/s	2,3		95		5.0						2.0				B381965	35.05	35.65	0.227			VA05060235	0.60
2	6	1.0	2.0	70	10	1	k/s	3	2	60					40.0			5.0				B381966	35.65	36.45	0.104			VA05060235	0.80
5	6	1.0	2.2	35	25	1	k/s	3,1	2	60		20.0			20.0			2.0				B381967	36.45	37.20	0.474			VA05060235	0.75
4	6	0.5	2.0	10	45	2	k/s	1	0	60					40.0			3.0				B381968	37.20	38.10	0.124			VA05060235	0.90
4	6	0.5	2.0	10	45	2	k/s	1	0	60					40.0			3.0				B381969	37.20	38.10	0.114	PD/CA		VA05060235	0.90
																						B381970	STANDARD 7G		4.530	7G		VA05060235	
8	6	0.5	4.0	25	65	0.5	k/q	1,2	3	60					40.0			4.0				B381971	38.10	39.62	0.183			VA05060235	1.52
2	6	1.5	2.5	20		1	k/q	3,1	3	40	5.0		5.0		30.0			4.0				B381972	39.62	39.88	0.364			VA05058633	0.26
2	2	0.5	1.0	10		1	k	2	0													B381973	39.88	41.15	0.018			VA05058633	1.27
1	1	0.5		60		0.4	q	1	0				0.1																
3	6	0.5	1.0	20		1	q/k	2	0	40								5.0				B381974	41.15	42.67	0.014			VA05058633	1.52
1	2	0.5	0.5	20		1	q	2	0	10								5.0											
3	6	1.0	2.0	15		1	q/s	2,1	0	70								3.0				B381975	42.67	43.35	0.082			VA05058633	0.68
							k	2														B381976	BLANK		<0.005			VA05058633	
3	6	0.2	0.6	10	90		s/chl	4,3	0	100								4.0				B381977	43.35	44.20	0.048			VA05060235	0.85
2	6	0.2	0.4	25	65		s/chl	4,2	0	100								4.0				B381978	44.20	45.72	0.065			VA05060235	1.52
2	6	0.3	0.5	30	75		s/chl	4,2	0	60			40.0					4.0	0.0			B381979	45.72	47.24	0.025			VA05060235	1.52
	6	0.4	1.0	35	20		s/chl	4,1	0	60			40.0					4.0				B381980	47.24	48.77	0.137			VA05060235	1.53
6	6	0.6	2.0	40	20		q/s	2,4	0	70			30.0					3.0				B381981	48.77	50.29	0.280			VA05060235	1.52
6	6	0.6	2.0	40	20		q/s	2,4	0	70			30.0					3.0				B381982	48.77	50.29	0.160	DUP		VA05060235	1.52
4	6	0.5	1.2	60	55		s/chl	4,1	0	90			10.0					2.0				B381983	50.29	51.82	0.175			VA05060235	1.53
2	6	0.6	1.0	35	10		s	4	0	100								4.0				B381984	51.82	52.54	0.045			VA05060235	0.72
3	1	0.5	1.2	25	50	1.5	q/s	2,4	0				20.0									B381985	52.54	53.34	0.027		vns radiating	VA05060235	0.80
3	4	0.3	0.9	75		10	cb/chl	2,3																					
3	6	0.5	1.1	45	60	20	q/s	3	0	20			50.0					4.0				B381986	53.34	54.86	0.047			VA05060235	1.52
4	6	2.0	2.6	30	60	20	q/s	3,2	1	50			40.0					2.0				B381987	54.86	56.35	0.175			VA05060235	1.49
							s/chl	4,1																					
5	6	1.0	2.0	40	70	10	q/cb	2,1	1	50			10.0					4.0				B381988	56.35	57.74	0.097			VA05058633	1.39
5	6	1.0	2.0	40	70	10	q/cb	2,1	1	50			10.0					4.0				B381989	56.35	57.74	0.104	PD/CA		VA05058633	1.39
																						B381990	STANDARD 2B		3.230	2B		VA05058633	
4	6	1.0	1.6	25		20	q/chl	3,1	0	30			40.0					3.0				B381991	57.74	59.07	0.132			VA05058633	1.33
							s	3																					
1	6	0.5	0.5	25		3	q/s	3	0				40.0						2.0			B381992	59.07	59.44	0.235			VA05058633	0.37
5	6	0.2	1.0	35		1	q/cb	3,1	0	10			40.0					4.0				B381993	59.44	60.96	0.048			VA05058633	1.52
10	1	0.2	2.0	35	75	1	s/chl	3,2	0	15								4.0											
4	6	0.5	1.2	35		2	q/cb	3,1	0	40			20.0					4.0				B381994	60.96	62.48	0.201			VA05060235	1.52
10	1	0.2	2.0	35	75	2	q/chl	4,2		15								4.0											
2	1	0.3	0.6	70		1	q/cb	4,2		3								0.0				B381995	62.48	64.01	0.035			VA05060235	1.53
3	6	0.2	0.6	50	60	10	q/s	2,4	0	40			40.0					4.0				B381996	BLANK		<0.005			VA05060235	
							chl/cb	3,2																					
8	6	0.3	1.6	35	60	10	q/s	2,4		20			60.0					2.0				B381997	64.01	65.40	0.070			VA05060235	1.39
							chl/cb	3,2																					
3	6	3.0	5.0	35		27	s/chl	4,3	2	80			20.0					3.0				B381998	65.40	66.17	0.683			VA05060235	0.77
							q/cb	2																					
1	6	0.3	0.3	40		5	s/q	4,3	2	85								4.0				B381999	66.17	67.06	0.023			VA05060235	0.89
5	6	0.6	1.6	60	45	5	q/s	1,4	0	30			40.0					4.0				B382000	67.06	68.58	0.062			VA05060235	1.52
2	6	0.5	1.0	70		40	q/s	3,2	2	30			15.0					3.0				B382001	68.58	68.96	0.151			VA05060235	0.38
							chl	3																					
2	6	0.5	1.0	70		40	q/s	3,2	2	30			15.0					3.0				B382002	68.58	68.96	0.118	DUP		VA05060235	

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 5 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		73.68	74.68	Extreme alt'n surrounds 5 sulphide vns, no orig GND texture, all alt'd out.	0	4	3	3	2	
10		74.68	77.72	Carbonate veinlets throughout section, approx 5 per 10cm interval. Highly alt'd section. Only relict qtz and bt remnants of GND texture. Overall colour greenish white to pale grey.	0	4	1	2	2	
10		77.72	80.22	Carbonate pervasive in 20cm and 50cm lengths, separated by 25cm of moderately alt'd GND (minor cb, chl, and silicified) around sulphide vein. From 79.25 to 80.22m, rock is this mod alt'd coherent core.	1	3	2	2	3	
10		80.22	82.00	Extremely alt'd GND. Sericite and carbonate pervasive. Entire section is too crumbly to remove from box in core form. 1-2mm bt grains evenly distributed are the only remaining GND texture. Veins no longer visible. Few wisps of sulphides and linear crumbles of carbonate but nothing definitive.	2	5	3	3	4	
10		82.00	85.62	Mod alt'd GND. Texture preserved through predominantly carb-alt'd rock. Veinlets randomly oriented and pervasive through matrix of GND. Po appears as subhedral grains within qtz/carb veins with grey qtz (max. 0.5cm) within milky qtz/carb selvage.	0	1	1	0	3	
10		85.62	91.44	Zone of high alt'n. Carb + chl + ser pervasive so rock is soft and crumbly. Overall colour is greenish pale grey. Sulphide veins at 86.15m (1cm) and at 89.4m (0.5cm).	0	3	3	0	3	
10		91.44	91.94	Selvage and vein sample. Vein is grey qtz with ~20% sulphides (ox'd py and aspy). Selvage shows high alt'n. Sulphides concentrated in centre of vein in 1cm wide section. Few 1-2mm lenses w/in qtz vein as well.	0	3	3	1	3	
10		91.94	95.19	Low to mod alt'n. GND texture preserved between carbonate veinlets and qtz/carb veins, which have chloritized selvages.	0	1	2	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	6	0.3	1.2	60	60	2	q/s	3	1	20			60.0					5.0				B382003	68.96	70.10	**0.131**			VA05060235	1.14
							chl/cb	1,2																					
5	1	0.5	2.5	70	35	2	q/s	3	0	10			20.0					2.0	0.0			B382004	70.10	71.63	**0.076**		slickenside s assc'd w/ carb	VA05060235	1.53
2	4	0.5	1.0	30		4	cb/s	4,3	0	30								4.0											
3	4	0.6	1.5	20	10	5	q/cb	3,2	3	5								5.0				B382005	71.63	73.15	**0.107**			VA05060235	1.52
3	1	0.6	1.5	50	80	1	q/cb	3	0				30.0																
1	6	1.5	1.5	80		20	q/cb	3,1	1	60			10.0					4.0											
							s	3	0																				
1	4	0.5	0.5	10		2	cb/s	2	1				2.0						4.0			B382006	73.15	73.68	**0.059**			VA05060235	0.53
							chl	2																					
5	6	0.8	1.6	35		4	cb/q	3,2	0	60			40.0					5.0	0.0			B382007	73.68	74.68	**0.088**		slickenside s in aspy	VA05060235	1.00
2	1	1.5	2.0	70		0.5	q	3	0				15.0									B382008	74.68	76.20	**0.062**			VA05060235	1.52
2	1	1.5	2.0	70		0.5	q	3	0				15.0									B382009	74.68	76.20	**0.061**	PD/CA		VA05060235	1.52
																						B382010	STANDARD 6F		**2.820**	6F		VA05060235	
2	4	0.5	1.0	20		0.5	cb/q	3,1	0	5								5.0				B382011	76.20	77.72	**0.039**			VA05060235	1.52
3	1	0.8	1.8	35	50	1	q/chl	3,1					20.0																
2	1	0.6	1.2	40		15	q/chl	2,3	0				20.0					5.0				B382012	77.72	79.25	**0.048**			VA05060235	1.53
4	4	2.0	6.0	50	150	50	cb/chl	5,2	0	5								5.0											
1	6	0.5	0.5	40		15	q/chl	2,4	0	80								2.0											
							cb	3																					
1	6	0.5	0.5	30		4	cb/q	1,2	0	60								4.0				B382013	79.25	80.22	**0.025**			VA05058633	0.97
0																						B382014	80.22	81.24	**0.048**			VA05058633	1.02
0																						B382015	81.24	82.00	**0.103**			VA05058633	0.76
																						B382016	BLANK		**<0.005**			VA05058633	
2	4	0.5	1.0	70	45	4	cb	4	1	5								5.0				B382017	82.00	82.62	**0.037**			VA05058633	0.62
6	3	0.2	1.2	65		1	q/cb	3	0						3.0			2.0				B382018	82.62	83.82	**0.027**		grey qtz w/in milky qtz	VA05060235	1.20
2	4	0.3	0.6	45		1	cb/chl	3	0																				
8	3	0.5	3.0	65		2	q/cb	3	0		5.0											B382019	83.82	85.34	**0.047**			VA05060235	1.52
2	3	0.4	0.8	70		1.5	q/cb	3	0		3.0											B382020	85.34	85.62	**0.021**			VA05060235	0.28
1	8	3.0	3.0	35		30	cb	4	2	20			10.0					5.0	0.0			B382021	85.62	86.87	**0.196**			VA05060235	1.25
1	3	10.0	10.0	50		20	cb/q	3,2	0				20.0	10.0															
							chl	2																					
1	3	10.0	10.0	50		20	cb/q	3,2	0				20.0	10.0								B382022	85.62	86.87	**0.468**	DUP		VA05058633	1.25
3	3	0.3	0.9	65		1	q/cb	3	0													B382023	86.87	88.39	**0.050**			VA05058633	1.52
							chl	1																					
3	6	0.5	1.5	45		20	q/chl	2		10			15.0					5.0	1.0										
							s/cb	3																					
2	1	1.2	1.8	55	45	2	q/chl	3	0				20.0						2.0			B382024	88.39	89.92	**0.103**			VA05058633	1.53
1	3	0.5	0.5	55		0																							
4	1	0.5	1.2	35	155	4	q/chl	4	0				20.0						1.0			B382025	89.92	91.44	**0.072**			VA05058633	1.52
							cb/s	1																					
1	6	0.5	0.5	50		0.5	q/cb	2		60			10.0					5.0											
1	1	10.0	10.0	50		40	chl/cb	3		20			10.0					4.0				B382026	91.44	91.94	**0.209**			VA05060235	0.50
							q/s	1,3																					
2	3	1.0	2.0	50		3	q/chl	3					15.0						1.0			B382027	91.94	92.96	**0.083**			VA05060235	1.02
							cb/s	2																					
3	3	0.5	1.5	50		2	q/chl	3	0		8.0		5.0						1.0			B382028	92.96	94.49	**0.053**			VA05060235	1.53
							cb	2																					
3	3	0.5	1.5	50		2	q/chl	3	0		8.0		5.0						1.0			B382029	92.96	94.49	**0.052**	PD/CA		VA05060235	1.53

DRILL LOG LEGEND P1	DATE: July 4-8, 2005 PAGE 7 of 16		
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		95.19	96.72	Mod to highly alt'd GND. Chl+carb alt'n pervasive, plus silicification makes texture grade to cryptocrystalline but GND texture still visible in 10% of sample.	0	2	3	0	3	
10		96.72	97.83	Highly alt'd GND. Carb+chl+ser alt'n pervasive such that rock is easily broken, but coherent. 10% preservation of GND texture.	0	4	4	2	4	
10		97.83	101.92	Highly alt'd GND. Carb/chl/ser alt'n pervasive. Rock is highly broken and crumbly, as alt'n is throughout matrix.	0	4	4	3	4	
10		101.92	102.66	Unalt'd GND w/ qtz veins w/ very few sulphides and small selvages	0	1	1	0	0	
10		102.66	111.25	Carb-infused GND. Crumbling to coarse sand texture w/ no longer than 15cm lengths of competent rock. Recovery is good (65-70%), but quality so poor, veins are not readily visible; count is probably low. Disseminated aspy throughout GND.	0	1	1	2	4	
10		111.25	115.26	More competent GND. 60% competent rock sulphide/carb veins may have started as only sulph veins; carb secondary. Crumbly section abuts competent at 17° to CA.	0	1	1	1	2	
10		115.26	119.78	90% competent GND. Crumbly carb-infused sections (1-12cm wide) make up 10% of section and intersect at 25° to 40° with sharp boundaries. Sample from 115.82 to 116.71m contains one crumbly section with sulph vein adjacent to 25cm long section of 'bleached'/carbonitic GND w/ texture preserved. Colour is orange-green beige. (orange=siderite (ox'd carb), green = chl). From 117.35 to 118.15m, another alt'd section (2 samples). There are at least 2 generations of qtz veining here, plus the carb. Latest qtz episode is most visible, so these veins are noted. Aspy throughout width of vein (not selvage).	0	1	1	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B382030	STANDARD 6F		2.730	6F		VA05060235	
4	3	1.0	2.0	50		4	q/chl	3	0		4.0		20.0									B382031	94.49	95.19	0.090			VA05060235	0.70
							cb/s	2																					
5	6	1.5	4.0	40	70	20	q/cb	1,4	0	40			10.0					3.0				B382032	95.19	96.20	0.115			VA05060235	1.01
							chl/s	3																					
4	1	0.8	3.2	65	45	4	q/chl	3					30.0									B382033	96.20	96.72	0.058			VA05060235	0.52
							cb	3																					
1	1	0.5	0.5	60		6	q/chl	3		10			3.0					4.0	1.0			B382034	96.72	97.83	0.045			VA05060235	1.11
							cb/s	3																					
3	6	1.0	1.4	55		5	q/cb	4		50								5.0											
							chl/s	2																					
6	1	1.0	5.0	60	30	5	q/chl	3		15			10.0					3.0				B382035	97.83	99.06	0.082			VA05060235	1.23
							cb/s	4																					
																						B382036	BLANK		<0.005			VA05060235	
1	6	6.0	6.0	30		30	cb/s	4		60	2.0		5.0					4.0				B382037	99.06	99.60	0.496			VA05060235	0.54
							chl	4																					
10	1	1.0	6.0	30	60	3	q/cb	4					10.0						2.0			B382038	99.60	100.58	0.153			VA05060235	0.98
							chl/s	2																					
3	1	0.5	1.5	30	60	15	chl/cb	4					15.0						3.0			B382039	100.58	101.92	0.082			VA05060235	1.34
							q/s	2																					
3	3	1.0	2.5	90	40	1	q/cb	3					3.0									B382040	101.92	102.66	0.024			VA05060235	0.74
							chl	3																					
	3	0.5	1.0	30		2	cb/s	4	0													B382041	102.66	103.63	0.035			VA05060235	0.97
							chl/q	3																					
2	3	0.5	1.0	30		2	cb/s	4	0													B382042	102.66	103.63	0.027	DUP		VA05060235	0.97
2	3	1.0	2.0	50		10	chl/cb	1,4	1	5								5.0				B382043	103.63	105.16	0.022			VA05060235	1.53
7	3	0.5	3.5	35		4	q/chl	4					10.0						2.0			B382044	105.16	106.68	0.072			VA05060235	1.52
							cb	2																					
7	1	0.3	2.1	45		2	q/cb	3,2			2.0		15.0									B382045	106.68	108.20	0.058			VA05060235	1.52
							chl	1																					
8	1	0.5	3.5	10	45	2	q/cb	3					20.0						3.0			B382046	108.20	109.73	0.051			VA05058633	1.53
							chl	1																					
4	1	1.0	4.0	65		3	q/chl	3					30.0					2.0				B382047	109.73	111.25	0.105			VA05058633	1.52
							cb	3																					
3	4	0.3	0.9	30	50	2	cb/s	3,2																					
2	1	0.5	1.0	50		2	q/cb	.					15.0									B382048	111.25	112.78	0.430			VA05058633	1.53
8	3	0.5	4.0	50		1	q/cb	2,3					40.0						1.0										
							chl	2																					
8	3	0.5	4.0	50		1	q/cb	2,3					40.0						1.0			B382049	111.25	112.78	0.076	PD/CA		VA05058633	1.53
																						B382050	STANDARD 1A		0.887	1A		VA05058633	
5	1	1.0	3.0	50	30	6	q/cb	3					60.0									B382051	112.78	114.30	0.166			VA05060235	1.52
							chl	3																					
4	1	0.5	2.0	50	30	2	q/cb	3					50.0									B382052	114.30	115.26	0.183			VA05060235	0.96
							chl	1																					
7	1	2.0	4.0	30	40	4	q/chl	3					40.0									B382053	115.26	115.82	0.376			VA05060235	0.56
1	8	2.0	2.0	40		10	cb/s	5	1	20								5.0				B382054	115.82	116.71	0.240			VA05060235	0.89
8	1	5.0	8.5	40	55	4	q/cb	2,3		10			20.0					5.0											
							chl	1																					
7	1	0.8	2.8	35		12	q/chl	2,4	0				20.0									B382055	116.71	117.35	0.141			VA05060235	0.64
							cb	3																					
																						B382056	BLANK		<0.005			VA05060235	

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 9 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		119.78	121.92	Fewer qtz veins continue into silicified GND. Colour is med grey, texture cryptocrystalline except speckles of 1mm bt. Rock readily breaks on randomly oriented veinlets of carbonate.	0	0	1	0	1	
10		121.92	124.97	Silicified GND infused with carb; rock is soft and crumbly. Veinlets of calcite generally run at 45° to CA, so breakage is predominantly on this angle as well. 20% soft carb-clay. Slickensides in carb veins.	0	1	1	1	3	
10		124.97	129.54	Back to less-carbonitized, silicified GND (as 119.78-121.92m), veinlets of carb at lower angle	0	0	1	0	1	
10		129.54	131.71	Gradation back to unsilicified GND. Qtz veins w/ carb/chl selvages more prominent. Aspy is 1-2mm, w/in qtz veins, not ox'd or alt'd. From 131.06 to 131.71m, 2 qtz veins and 2 sulph veins account for entire sample's alt'n (65cm chl'd and cb'd to yellowish green)	0	0	3	1	2	
10		131.71	134.56	Carb-infused cryptocrystalline, silicified GND w/ numerous qtz veins. 50% carb-clay crumbles. Sulphide 'veins' attached to edges of carb veins and/or qtz veins.	0	1	2	3	3	
10		134.56	135.39	Unalt'd GND (not silicified), w/ 20% carb-clay crumbles.	0	0	1	1	1	
10		135.39	137.80	Silicified cryptocrystalline GND w/ qtz veins with large chl'd selvages. Carb veinlets in random orientations - web appearance - cause breakage of otherwise competent core. (<5% clay). Good potential for gold here. <1mm flecks seen	0	0	1	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 6 = quartz/chlorite, 8 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other			From	To					
3	1	0.4	1.2	50		55	q/chl	2,4	1	25								4.0				B382057	117.35	117.90	0.139		following two samples are one selvage, total 80cm	VA05060235	0.55
							cb	3																					
2	6	1.2	20.0	60						100								4.0												
1	4	1.2	1.2	30		25	q/chl	2,4	1													B382058	117.90	118.15	0.241			VA05060235	0.25
2	8	4.0	7.0	30			cb	3																						
4	1	2.0	6.0	30	50	3	q/chl	4	0				20.0						1.0			B382059	118.15	118.87	0.114			VA05060235	0.72
							cb	1																						
11	1	3.0	8.5	50	70	15	q/chl	4	0				1.0									B382060	118.87	119.78	0.181			VA05060235	0.91
							cb	1																						
4	1	0.5	2.0	35	20	4	q/chl	3	0				10.0									B382061	119.78	120.40	0.027			VA05060235	0.62
							cb	1																						
4	1	0.5	2.0	35	20	4	q/chl	3	0				10.0									B382062	119.78	120.40	0.019	DUP		VA05060235	0.62
1	1	0.4	0.4	35		1	chl/cb	1					5.0					1.0				B382063	120.40	121.92	0.053			VA05058633	1.52
							q	3																						
3	1	0.4	1.2	150		5	q/chl	3,2					20.0					2.0				B382064	121.92	123.44	0.079			VA05058633	1.52
4	4	0.3	1.2	50	10	0.4	cb	3														B382065	123.44	124.97	0.095			VA05058633	1.53
7	4	1.0	2.2	40		0.5	cb/s	3,1																						
2	1	0.3	0.6	25		1.5	q/chl	3					15.0																	
							cb	2																						
3	4	0.3	0.9	25		1.5	cb	2														B382066	124.97	126.49	0.039			VA05058633	1.52
5	1	1.0	3.0	40	25	4	q/chl	4	0				15.0									B382067	126.49	128.02	0.041			VA05058633	1.53
							cb	2																						
6	1	1.5	2.5	40	45	5	q/chl	4					15.0									B382068	128.02	129.54	0.136			VA05058633	1.52
							cb	2																						
6	1	1.5	2.5	40	45	5	q/chl	4					15.0									B382069	128.02	129.54	0.191	PD/CA		VA05058633	1.52
																						B382070	STANDARD 5E		1.440	5E		VA05058633	
7	1	1.0	4.5	35	30	8	q/chl	4					15.0									B382071	129.54	130.28	0.099			VA05058633	0.74
							cb	3																						
7	1	0.5	3.5	30	25	4	q/chl	4					15.0									B382072	130.28	131.06	0.282			VA05058633	0.78
							cb	3																						
2	1	0.5	1.0	40		25	q/chl	4					5.0									B382073	131.06	131.71	0.205			VA05058633	0.65
							cb	3																						
2	6	0.6	0.9	40		40	q/chl	4		20			30.0					4.0												
							cb	4																						
6	1	1.0	3.5	50	30	6	q/chl	4					15.0					2.0				B382074	131.71	132.83	0.097			VA05058633	1.12
							cb/s	3,1																						
3	3	2.0	4.0	170		0							3.0																	
3	1	1.0	3.0	40	4		q/chl	4					10.0					3.0												
							cb/s	1																						
3	3	1.0	2.0	150	0																	B382075	132.83	134.11	0.053			VA05058633	1.28
																						B382076	BLANK		<0.005			VA05060567	
2	6	0.5	1.0	150	170	8	cb	5	0	80								5.0				B382077	134.11	134.56	0.130		sulph. appears as black clay (ox'd py (?))	VA05060567	0.45
							chl/s	1																						
5	1	1.0	4.0	40		2	q/chl	3					10.0									B382078	134.56	135.39	0.040			VA05060567	0.83
							cb	1																						
2	4	1.5	2.0	30		1	cb	3																						
3	1	0.7	1.3	35	50	4	q/chl	4					5.0									B382079	135.39	136.40	0.021			VA05060567	1.01
							cb	3																						

DRILL LOG LEGEND - P1

DRILL HOLE # : DG05-290C

DATE: July 4-8, 2005 PAGE 11 of 16

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		137.80	139.08	Section v. broken up. Influx of carb.	0	0	1	2	3	
10		139.08	141.62	Unalt'd GND w/ qtz veins with carb/chl'd selvages. Solid rock.	0	0	1	0	1	
10		141.62	144.78	50% unalt'd GND w/ qtz veins, 50% highly alt'd around carb-infused sections, at 60° to CA. Carb'd sections are crumbly at centre (max 20cm) with competent, yellow-white surrounding selvages (up to 10cm on either side). Slickensides in sulphides (aspy and py) at margins of qtz/carb/sulph veins	0	1	1	1	2	
10		144.78	146.21	Zone of extreme alt'n. GND texture barely visible beneath carb/chl alt'n, causing rock to be soft but still competent. Lenses of sulphides on carb veins show moderate slickensides	0	2	4	2	4	
10		146.21	153.53	Qtz veins with selvages continue into zone of greater carb alt'n in veinlets and through matrix of ~40% of section, causing crumbly/competent alternating sections approx 20cm long, ave. Late carb veins overprint old qtz veins and incorporate sulphides (from qtz to carb vein). Veins are at 120° to each other.	0	1	2	2	2	
10		153.53	161.24	Carb-infused GND. Competent sections <15cm long. Carb veining is wider than before: approx. 5-10% of sample is pure calcite!	0	1	2	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	1.0	3.0	40	25	6	q/chl	4		20			5.0									B382080	136.40	137.16	0.026			VA05060235	0.76
							cb	2																					
7	1	1.2	4.2	40		5	q/chl	4	0	10			15.0									B382081	137.16	137.80	0.198			VA05060235	0.64
							cb	2																					
7	1	1.2	4.2	40		5	q/chl	4	0	10			15.0									B382082	137.16	137.80	0.072	DUP		VA05060235	0.64
8	1	0.5	2.0	40	50	3	q/chl	4					15.0									B382083	137.80	138.68	0.098			VA05060235	0.88
							cb	2																					
2	4	0.5	1.0	70		0.4	cb	4																					
4	4	0.5	2.0	25		4	cb	4														B382084	138.68	139.08	0.014			VA05060235	0.40
6	1	0.5	3.0	40	160	2	q/chl	3,1			3.0		5.0						2.0			B382085	139.08	140.21	0.047			VA05058633	1.13
6	3	1.0	4.0	30		2	q/cb	3		30																			
							chl	3																					
4	1	1.0	4.0	35	50	4	q/cb	3					20.0									B382086	140.21	141.09	0.131			VA05058633	0.88
							chl	3																					
4	3	1.0	4.0	60		6	q/cb	3		5			10.0					2.0				B382087	141.09	141.62	0.025			VA05058633	0.53
							chl	2																					
1	3	20.0	20.0	45		20	q/cb	4					15.0					2.0				B382088	141.62	142.25	0.502			VA05058633	0.63
							chl	1																					
1	3	20.0	20.0	45		20	q/cb	4					15.0					2.0				B382089	141.62	142.25	0.012	PD/CA		VA05060235	0.63
																						B382090	STANDARD 7G		4.390	7G		VA05060235	
3	1	2.0	5.0	30	75	4	q/chl	3					10.0						1.0			B382091	142.25	143.26	0.206			VA05060235	1.01
:	6	1.0	1.6	40		20	q/chl	3	1	40			20.0					4.0											
							cb	3																					
1	6	0.6	0.6	20		0.4	q	2	0				70.0																
5	4	0.3	0.9	45		10	cb	3														B382092	143.26	144.78	0.060			VA05060235	1.52
5	1	2.5	4.4	30		8	q/chl	3					15.0																
							cb	1																					
2	1	1.5	2.5	40	50	6	q/chl	2					15.0									B382093	144.78	146.21	0.046			VA05060235	1.43
							cb	3																					
2	3	1.8	3.0	45		10	cb	4		10								5.0											
							q/chl	3																					
2	1	1.0	1.5	65		1	q/chl	3					10.0									B382094	146.21	146.95	0.034			VA05060235	0.74
3	1	1.0	3.0	30	50	3	q/chl	3					5.0						2.0			B382095	146.95	147.83	0.030			VA05060235	0.88
3	3	2.0	5.0	50		1	cb	2														B382096	BLANK		<0.005			VA05060235	
3	1	1.0	1.6	60		8	q/chl	4	1	10			10.0					5.0				B382097	147.83	148.65	0.054		slickens in sulphides	VA05060235	0.82
							cb	3																					
6	1	1.0	3.0	30	120	1	q/chl	3					30.0									B382098	148.65	149.35	0.121		veins not visible; only crumbly selvage	VA05060235	0.70
2	4			45		12	cb	4																					
6	1	0.5	3.0	40	50	1	q/cb	4					20.0					1.0				B382099	149.35	150.88	0.072			VA05060237	1.53
							chl	1																					
2	4	0.5	1.0	50	140	1	cb	3																					
4	1	3.0	5.2	60	20	8	cb/chl	4					10.0									B382100	150.88	152.40	0.061			VA05060237	1.52
							q	3																					
1	6	0.7	0.7	70		3	q/chl	4,1																					
4	1	0.5	1.4	30	60	1	q/chl	4,1					10.0						2.0			B382101	152.40	153.53	0.018			VA05060237	1.13
3	4	0.5	1.5	150		2.5	cb	3																					
4	1	0.5	1.4	30	60	1	q/chl	4,1					10.0						2.0			B382102	152.40	153.53	0.020	DUP		VA05060237	1.13
1	1	0.5	0.5	40		1	q/chl	3,2					2.0						4.0			B382103	153.53	153.92	0.013			VA05060237	0.39
9	1	0.5	4.5	60	20	6	q/chl	3,1				5.0										B382104	153.92	155.45	0.028			VA05060237	1.53
7	1	0.5	3.5	50	130																	B382105	155.45	156.97	0.028			VA05060237	1.52

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 13 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.24	161.99	GND is competent but highly alt'd with carb and chl, and is silicified around 6 sulphide-rich veins. On broken face more old qtz veins are visible but highly silicified. Mod slickensides on sulph-vein face.	1	0	3	0	4	
10		161.99	163.67	Relatively unalt'd section; carb influx, sections crumbly	0	1	2	2	3	
10		163.67	166.12	Highly to extremely alt'd GND. Carbonate pervasive across competent and incompetent ("carb-clay-crumbie") sections. 60% crumbly.	1	1	3	3	4	
10		166.12	167.61	Selvage and 15cm sulphide vein. Upper selvage is more carbonitized (crumbly), than lower selvage (competent). Lower selvage contains 2 qtz veins (may help to explain less carb down there).	1	1	3	1	3	
10		167.61	168.82	Numerous grey-milky qtz veins w/ lots of aspy (2 samples)	1	1	3	0	2	
10		168.82	175.26	Moderately silicified GND with ~30cm sections of carb-infused, crumbly rock. Qtz veins visible in competent sections and as linear relicts qtz pebbles. ~50% of section is broken up, crumbly rock.	1	2	3	1	3	
10		175.26	181.36	Highly to extremely alt'd GND silicified plus chl/cb selvage alt'n around sheeted qtz veins and sulphides. Slickensides seen on sulph vein faces, in ox'd py and ser and calcite.	1	2	3	1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
4	1	1.0	2.5	20	40	4	q/chl	2			5.0		15.0									B382106	156.97	157.55	0.095			VA05060237	0.58
							cb	2																				
1	1	1.5	1.5	50		25	cb	5		25			5.0					4.0				B382107	157.55	158.96	0.071		mod. slickens on sulph vein	VA05060237	1.41
1	6	0.8	0.8	140		8	q/cb	3,4		65			10.0					4.0											
4	1	1.0	3.0	35		2	q	4					10.0									B382108	158.96	160.02	0.100			VA05060237	1.06
4	4	1.0	4.0	25		6	cb	4																				
4	4	1.0	4.0	25		6	cb	4														B382109	158.96	160.02	0.108	PD/CA		VA05060237	1.06
																						B382110	STANDARD 1A		0.979	1A		VA05060237	
5	3	1.0	3.0	60	30	5	q/cb	4	1				5.0									B382111	160.02	161.24	0.029			VA05060237	1.22
3	6	0.5	0.8	60	40	4	q/cb	4	1	90								4.0				B382112	161.24	161.99	0.249			VA05060237	0.75
4	1	1.0	3.5	50	70	2	q/cb	3	1				5.0									B382113	161.99	163.07	0.032			VA05060237	1.08
6	1	0.7	3.2	65	40	3	q/cb	3	1				10.0						3.0			B382114	163.07	163.67	0.045			VA05060237	0.60
2	4	0.3	0.6	150		0																						
5	6	0.5	2.4	40	60	10	q/cb	4		50			15.0	5.0				4.0				B382115	163.67	164.59	0.262			VA05060237	0.92
							chl/s	3,1																				
																						B382116	BLANK		<0.005			VA05058634	
2	1	1.0	2.0	65		15	q/cb	2,4	0				5.0									B382117	164.59	165.06	0.125			VA05058634	0.47
							chl	2																				
1	3	1.0	1.0	145		0							5.0						4.0									
4	1	1.0	4.0	80	70	2	q/chl	3	0				8.0						1.0			B382118	165.06	166.12	0.044			VA05058634	1.06
1	6	15.0	15.0	35		137	q/chl	4,3		75	2.0	10.0				1.0		2.0				B382119	166.12	167.61	4.850			VA05058634	1.49
							cb/s	3,1																				
2	1	0.6	1.0	60	70	0																						
6	1	1.0	5.0	35		20	q/chl	4,3	1	5			30.0						1.0			B382120	167.61	168.23	0.290			VA05058634	0.62
							cb	1																				
5	1	1.0	3.0	50	30	10	chl/cb	3	1				15.0						1.0			B382121	168.23	168.82	0.024			VA05058634	0.59
							q	3																				
5	1	1.0	3.0	50	30	10	chl/cb	3	1				15.0						1.0			B382122	168.23	168.82	0.019	DUP		VA05058634	0.59
2	1	0.5	1.0	25	70	1	q	3					25.0									B382123	168.82	169.16	0.024			VA05058634	0.34
9	1	2.0	11.0	50	20	3	q/chl	4,2					10.0						2.0			B382124	169.16	170.49	0.035			VA05058634	1.33
							cb	3																				
7	1	1.0	5.0	30	60	4	q/chl	4,2					10.0						1.0			B382125	170.49	171.51	0.021			VA05060237	1.02
							cb	3																				
6	1	0.5	2.0	40		4	q/chl	3			2.0		10.0									B382126	171.51	172.68	0.018			VA05060237	1.17
							cb	3																				
4	1	1.0	2.6	45		20	q/chl	3					5.0									B382127	172.68	173.74	0.125			VA05060237	1.06
							cb	3																				
1	6	0.3	0.3	40						5	5.0		40.0					5.0											
8	1	1.0	3.5	40	50	1	cb/q	3					5.0									B382128	173.74	175.26	0.028			VA05060237	1.52
8	1	1.0	3.5	40	50	1	cb/q	3					5.0									B382129	173.74	175.26	0.028	PD/CA		VA05060237	1.52
																						B382130	STANDARD 4D		0.435	4D		VA05060237	
7	1	1.2	5.0	40		4	q/chl	3					10.0						3.0			B382131	175.26	176.16	0.128			VA05060237	0.90
							cb	2																				
2	6	0.4	0.8	35		20	q/chl	3		30			70.0					2.0											
							cb	2																				
4	6	1.3	2.4	45	55	40	q/cb	4		80	5.0		10.0									B382132	176.16	176.78	0.350			VA05060237	0.62
							chl	2																				
1	1	0.5	0.5	50									5.0														same selvage as sulph veins above		
2	6	0.4	0.7	25			q/cb	4					70.0									B382133	176.78	178.31	0.069			VA05060237	1.53
							chl	3																				
5	1	2.0	4.5	60		10	q/cb	4					5.0									B382134	178.31	179.18	0.078			VA05060237	0.87

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 15 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		181.36	187.76	Unalt'd GND between selvages of qtz and sulphide veins. Less carbonate and fewer (but larger) veins. Unalt'd GND in between selvages, up to 50cm long, making up 25% of section. Slickensides in aspy on fract'd veinlet face. From 186.21-186.46m, carbonate is pervasive for 24cm. Clear boundaries at 80° to CA.	0	1	2	1	2	
10		187.76	190.20	Zone with qtz veins and large chl-cb selvages separated by unalt'd GND, in length up to 10cm (15% of section). Slickensides seen on broken sulphide vein face in ox'd py and ser.	1	1	2	1	2	
10		190.20	195.07	Unalt'd GND w/ small grey qtz/carb veins (<0.5cm, mostly). Few grey qtz veins up to 1cm wide; one grey qtz/carb vein 2cm wide. Veinlets of carbonate overprint qtz veins, sometimes using same pathway, others not. Approx 14 carb veinlets/metre.	0	0	1	0	1	
10		195.07	195.67	Top of section is 2cm qtz-carb-sulph vein, followed by 47cm of carb-infused crumbly GND w/ three 1cm sulph veins. One sulph vein (100% ox'd py) and 5cm selvage at end of sample.	1	1	1	2	3	
10		195.67	196.90	Unalt'd GND w/ aspy-rich qtz veins w/ small selvages	0	0	1	0	1	
			(EOH)							

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	2																					
2	4	0.4	0.8	45																							same selvage - 2 vein types		
3	6	0.3	0.9	30	140		q/cb	4														B382135	179.18	179.83	0.042			VA05060237	0.65
							chl	2																					
																						B382136	BLANK		<0.005			VA05060237	
4	1	1.0	4.0	60		40	q/cb	4					8.0									B382137	179.83	180.51	0.090			VA05060237	0.68
							chl	2																					
5	1	1.6	4.1	75	50	85	q/cb	4					5.0					5.0				B382138	180.51	181.36	0.180			VA05060237	0.85
							chl	2																					
2	6	0.6	0.9	40	65					70																	same selvage		
5	3	0.5	2.5	45	30	3	cb/q	3	0				20.0									B382139	181.36	182.88	0.128			VA05060237	1.52
							chl	3																					
8	1	12.0	19.0	35	50	14	cb/q	4	0	5			30.0									B382140	182.88	184.40	0.358			VA05058634	1.52
							chl	3																					
4	1	0.5	2.0	30		4	cb/q	2					30.0									B382141	184.40	185.49	0.086			VA05058634	1.09
							chl	1																					
4	1	0.5	2.0	30		4	cb/q	2					30.0									B382142	184.40	185.49	0.079	DUP		VA05058634	1.09
2	4	3.0	4.0	80		24	cb	4					10.0									B382143	185.49	186.46	0.054			VA05058634	0.97
3	1	20.0	22.0	60	50	10	q/cb	3					20.0									B382144	186.46	187.76	0.501			VA05058634	1.30
							chl	2																					
8	1	2.5	6.0	50	60	20	q/cb	3					10.0									B382145	187.76	188.77	0.168			VA05060237	1.01
							chl	2																					
1	6	1.2	1.2	55						30			60.0					4.0				B382146	188.77	190.20	0.122			VA05060237	1.43
3	1	0.5	1.1	50		0.2	q/chl	2	0				8.0									B382147	190.20	191.32	0.018			VA05060237	1.12
4	1	0.7	1.5	35	45	0.5	q/chl	2	0				5.0									B382148	191.32	192.02	0.034			VA05060237	0.70
4	1	0.7	1.5	35	45	0.5	q/chl	2	0				5.0									B382149	191.32	192.02	0.034	PD/CA		VA05060237	0.70
																						B382150	STANDARD 7G		4.520	7G		VA05060237	
7	1	0.6	2.4	30		1	q/cb	3		10			20.0									B382151	192.02	193.55	0.022			VA05060237	1.53
7	1	0.4	2.0	60		2	q/chl	0			3.0		3.0						1.0			B382152	193.55	195.07	0.024			VA05058634	1.52
							cb	2																					
1	3	2.0	2.0	55		10	cb/chl	3		20								4.0				B382153	195.07	195.67	0.202			VA05058634	0.60
							q/s	1																					
3	6	1.5	30.0	55	25	15	cb/chl	3		90			10.0					4.0												
							q/s	1																					
4	1	1.0	4.0	40		4	cb/chl	3					35.0									B382154	195.67	196.60	0.024			VA05058634	0.93
							q	1																					
3	1	1.0	2.0	50		4	cb/chl	3	0				40.0									B382155	196.60	196.90	0.094			VA05058634	0.30
							q	1																					
																						B382156	BLANK		<0.005			VA05058634	
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-291C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 936m

BEARING: 000 | DIP: -50°

DATE STARTED: 25-Jun-05 | DATE COMPLETED: 16-Jul-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459506 NORTHING: 7099243

COORD SYSTEM: NAD 83: EASTING: 459387 NORTHING: 7099427

NAD 27 (CORRECTED for historic grid): EASTING: 459476 NORTHING: 7099253

SECTION LINE(historic grid): 459476

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 5.18m

Deviation:

Casing: 5.18m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

SAMPLING DETAILS

Sample Sequence: B381879 to B381926

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Jul-05

Lab Record #: VA0506023, VA05058634 Date Received: 21-Jul-05, 16-Jul-05

Sample Sequence: B382157 to B382216

Requisition #: MASP448STRGOL.05Q Date Shipped: 15-Jul-05

Lab Record #: VA05060971 Date Received: 26-Jul-05

Sample Sequence: B382217 to B382333

Requisition #: MASP448STRGOL.05Q Date Shipped: 17-Jul-05

Lab Record #: VA05060214 Date Received: 22-Jul-05

Sample Sequence: B382334 to B382386

Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05

Lab Record #: VA05062470 Date Received: 27-Jul-05

Notes: Hole was abandoned June 26th due to encroaching forest fire. Reopened July 9th.

Duplicates:	B391882, B381902, B381922, B382162, B382182, B382202, B382222, B382242, B382262, B382282, B392302, B382322, B382342, B382362, BB382382
Preparation Duplicate/ Check Assay:	B391889, B381909, B382169, B382189, B382209, B382229, B382249, B382269, B382289, B382309, B382329, B382349, B382369,
Standards:	B391890(4D), B381910(6F), B382170(4D), B382190(5E), B392210(2B), B382230(6F), B382250(7G), B382270(3C), B382290(2B), B382310(4D), B382330(5E), B382350(6F), B382370(7G),
Blanks:	B381896, B381916, B382176, B382196, B382216, B382236, B382256, B382276, B382296, B382316, B382336, B382356, B382376

FROM	TO	LITHOLOGY
5.18	266.57	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
51.8	334.9	-51.0	000.9	001.9
125.0	336.1	-50.6	002.1	003.1
200.0	339.9	-46.6	005.9	006.9
266.7	341.5	-42.5	007.5	008.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 1 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-5.18m			CASING; no recovery						
10	5.18-266.57m			GND						
10		5.18	10.67	GND: 15% qtz, 20% feldspar, 30% hbl, 35% bt. Qtz veins (max 1cm) with silicified selvages, up to 20cm wide. Granular appearance w/ oxidation of feldspars to light yellowish orange. Hem ox'd to reddish black w/in veins (~5%). Calcite crystallized on veinlets/fracture faces. Overall, rock is fractured to crumbly sand texture. Xenolith of argillite w/in GND at 5.25m. Finely laminated, dark grey-black. Size is 6cm by 5cm. Type '3' veins are 85% grey, opaque qtz and 15% white opaque calcite throughout. Magnetite is <2mm grains, concentrated near margins of veins; hematite distributed in veins, grains <2mm, up to 8%.	1	0	0	0	1	
10		10.67	12.19	Broken to gravel-sized silicified GND. Mafic minerals reduced to <10%.	1	0	0	0	1	
10		12.19	13.72	More competent, slightly silicified GND. Texture predominantly erased.	1	0	0	0	1	
10		13.72	20.61	GND. Original composition (as at 5.18m). More competent. Only 5% of section is gravelly/sandy, rest are in sections up to 40cm long. Sulphides concentrated at margins (not within) of veins; veins are milky qtz, 50% have grey qtz <3mm wide in centres. Black ox'd magnetite seen on fracture faces. Between veins, thin film of black, <1mm. Metallic mineral, soft hexagonal to tabular, ox'd to black and green: chalcocite (?), throughout GND. Noticeable large grains, up to 1cm in diameter or 3cm long.	1	0	0	0	1	
10		20.61	21.79	V broken to sandy gravel texture. GND oxidized on fracture faces and throughout crumbly sections. Rusty orange brown ox'n product of hematite/limonite.	2	0	0	0	1	
10		21.79	28.50	Competent core with moderate recovery (65%); composition GND as at 5.18m (mafic). At 27.25m, aplite vein (4cm) is cross-cut by 1cm qtz vein. Aspy associated w/ aplite is conc at this intersection.	1	0	0	0	1	
10		28.50	31.32	Crumbly and broken GND. One 10cm gouge section w/ 10% clay, 90% sand, brown, contacts GND at 20°	2	0	0	1	1	
10		31.32	35.05	GND as at 5.18m	1	0	0	0	1	
10		35.05	45.72	50% unalt'd GND as above, 50% crumbly to sandy v. broken up rock. Alternates between them at 0.5m intervals. Recovery averages 50%. Most loss occurs at broken sections. Samples separated where changes occur.	2	0	0	1	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 25 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	iscordite	biotite	other		From	To					
5	3	0.8	3.8	30	60	2.0	q/cb	3,1	1													B381879	5.18	6.10	0.022			VA05060237	0.92
2	7	2.5	5.0	45		6.0	q/k	2,1	1																				
2	1	2.0	4.0			2.0	q	3	1													B381880	6.10	7.62	0.105		qtz in pieces	VA05060237	1.52
1	1	0.5	0.5	60		1.0	q	4	1													B381881	7.62	9.14	0.049			VA05060237	1.52
1	1	0.5	0.5	60		1.0	q	4	1													B381882	7.62	9.14	0.023	DUP		VA05060237	1.52
1	1	5.0	5.0	30		20.0	q	4	1													B381883	9.14	9.53	1.900			VA05060237	0.39
3	1	2.0	5.0	60		1.0	q	2	0													B381884	9.53	10.67	0.088			VA05060237	1.14
2	1	2.0	3.0			20.0	q	3	1													B381885	10.67	12.19	0.152			VA05060237	1.52
3	1	1.5	2.5	60	30	20.0	q	3	1													B381886	12.19	13.72	0.128			VA05060237	1.53
4	1	1.2	2.8	40	50	1.0	q/cb	2	1				5.0						1.0			B381887	13.72	15.24	0.061			VA05060237	1.52
3	1	1.0	3.0	60		1.0	q	2	1				10.0						1.0			B381888	15.24	16.76	0.122			VA05058634	1.52
1	7	6.0	6.0	55		5.0	q	2	1																				
1	7	6.0	6.0	55		5.0	q	2	1													B381889	15.24	16.76	0.069	PD/CA		VA05058634	1.52
																						B381890	STANDARD 4D		0.462	4D		VA05058634	
4	1	1.2	3.0	50		6.0	q	2	2	0.1			0.1					5.0				B381891	16.76	18.29	0.074			VA05058634	1.53
3	1	2.0	3.0	50		6.0	q/chl	3,1	1	6.0			5.0					2.0	1.0			B381892	18.29	19.81	0.043			VA05058634	1.52
							k	1																					
1	1	0.6	0.6	50		4.0	q/k	2	3				2.0						2.0			B381893	19.81	20.61	0.034			VA05060237	0.80
2	1	1.0	1.5	50		3.0	chl/q	2,1	1				2.0						3.0			B381894	20.61	21.79	0.011			VA05060237	1.18
5	1	1.2	4.3	25	60	1.0	q	1	2				3.0						0.0			B381895	21.79	22.91	0.249			VA05060237	1.12
																						B381896	BLANK		<0.005			VA05060237	
3	1	0.8	2.0	30	50	0.5	q	2	1				10.0						3.0			B381897	22.91	24.38	0.090			VA05058634	1.47
1	7	1.4	1.4	60		0.5	chl/k	1	1																		7=aplite dykes		
1	2	0.5	0.5	150		0.5	q/k	1,3	3								20.0	4.0									other=chalcocite		
3	2	1.0	3.0	20		2.0	q/k	3	3				5.0						4.0			B381898	24.38	25.91	0.049			VA05058634	1.53
							chl	1																					
1	1	3.0	3.0	60		1.0	q/chl	1	1								10.0												
3	1	2.0	3.5	50		2.0	q/cb	3,1	2	5.0			10.0				5.0	5.0	4.0			B381899	25.91	27.43	0.062			VA05058634	1.52
1	7	4.0	4.0	115		0.0							5.0						4.0										
1	2	0.5	0.5	55		0.5	q/k	1,2	2													B381900	27.43	28.50	0.567			VA05060237	1.07
1	1	1.0	1.0			1.0	q	1	1													B381901	28.50	29.49	0.155			VA05060237	0.99
1	1	1.0	1.0			1.0	q	1	1													B381902	28.50	29.49	0.109	DUP		VA05060237	0.99
0																						B381903	29.49	30.45	0.013			VA05060237	0.96
1	1	1.0	1.0			0.5	q	1	0													B381904	30.45	31.32	0.252			VA05060237	0.87
1	2	0.5	0.5			0.5	q/k	1	2																				
5	2	2.5	5.0	50		1.0	q/k	3,2	2	8.0			2.0					2.0				B381905	31.32	32.32	0.410			VA05060237	1.00
							chl	1																					
1	2	0.5	0.5	65		1.0	q/k	3,1	1													B381906	32.32	33.53	0.251			VA05060237	1.21
7	1	1.0	4.0	60	30	2.0	q/chl	3,2	1	10.0			8.0					5.0	2.0			B381907	33.53	35.05	0.257			VA05060237	1.52
3	1	0.5	1.5	50		2.0	q	3	1				2.0						1.0			B381908	35.05	36.58	1.185			VA05060237	1.53
3	1	0.5	1.5	50		2.0	q	3	1				2.0						1.0			B381909	35.05	36.58	1.050	PD/CA		VA05060237	1.53
																						B381910	STANDARD 6F		2.860	6F		VA05060237	
3	1	1.5	4.0	60		1.0	q	3	3	0.1								5.0				B381911	36.58	38.10	0.079			VA05060237	1.52
2	1	1.5	3.0	60		0.0				2.0								5.0				B381912	38.10	39.30	0.248			VA05060237	1.20
2	1	0.4	0.8	60	30	0.5	q	3	1	0.1												B381913	39.30	39.62	0.011			VA05060237	0.32
3	1	0.5	1.5	60		10.0	q/chl	3,1	3	3.0			2.0						4.0			B381914	39.62	41.15	0.077			VA05058634	1.53
							k	3																					
2	1	1.0	2.0	15		0.5	q	3	0	0.1								5.0				B381915	41.15	42.67	0.190			VA05058634	1.52
																						B381916	BLANK		<0.005			VA05058634	
5	1	1.0	4.5	45	150	2.0	q/chl	3,1	2	3.0								5.0				B381917	42.67	43.17	0.328			VA05058634	0.50
0																						B381918	43.17	44.05	0.016			VA05058634	0.88
3	1	1.0	3.0	30	60	1.0	q/cb	3	1	5.0								4.0				B381919	44.05	44.74	0.026			VA05060237	0.69
1	3	1.0	1.0	15		10.0	q/cb	4,3	3	0.1								5.0				B381920	44.74	45.72	0.049			VA05060237	0.98

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		45.72	49.76	Limonite coats fracture faces, 1mm thick. Opaque orange-med brown. Pervasive limonite through core at 46.0-49.76m	3	0	0	1	2	
10		49.76	51.82	GND as at 5.18m, broken with lim on fewer fract faces	2	0	0	1	1	
10		51.82	55.55	Dark grey, partially silicified GND. One 15cm broken up section at 52.40m to coarse sand texture (qtz eyes, etc). Minor limonite and calcite on fracture face, generally at 40° and 15° to CA. In qtz/carb veins, ox'n appears as limonite.	1	0	0	0	1	
10		55.55	57.91	V coarse-grained qtz-rich GND. Euhedral bt up to 6mm in diameter. Disseminated aspy throughout, assoc. w/ bt. Feldspars weathering to clay minerals. Coherent core, however, w/ moderate to good recovery. This rock appears to be alt'd due to veining, as its contact is at 45° to CA (same as veins). Lim staining in wide (up to 5cm) selvages around veinlets.	1	0	1	0	1	
10		57.91	62.48	Lim staining 80% pervasive over section of otherwise unalt'd GND. Qtz veins have small qtz-alt'd selvages dominated by lim. V minor chl in selvage of qtz vein @ 61.00m. GND texture preserved throughout.	3	0	0	0	1	
10		62.48	64.01	GND texture 90% erased in this section, to aphanitic dark grey. v. broken up w/ limonite in wider veins (~2mm) w/ calcite. at 63.70m, a 1.5cm angular qtz piece is surrounded by hexagonal shaped concentration of mafic (bt) material.	4	0	0	1	2	
10		64.01	68.58	Unalt'd GND w/ lim on fract faces (10°-30° to CA); qtz veins partially silicified. Older episodes of veining not recorded, because these veins are too difficult to distinguish well.	1				1	
10		68.58	70.25	GND. Very broken up w/ lim on regular fracture sets at 30° and 130°. Start out 'clean' and go to crumbly and more irregular. Two types qtz veins: (1) large, milky, and (2) small w/ thin, central grey qtz with milky selvages. Evidence of motion w/in minerals: shear bands along 2 planes of motion.	2			1	1	
10		70.25	71.94	Gradation from crumbly, ox'd and carb'd GND above to unalt'd GND below. Silicified selvage on one vein, none on other.	1				1	
10		71.94	75.49	Unalt'd GND. Straight and clear qtz veins w/ little silicified selvages. Po appears, and lots of scorodite w/ aspy.	0	0	0	0	0	
10		75.49	76.02	Extreme alt'n around 3 qtz veins. GND texture totally erased to clay texture. Sericitized, chloritized and ox'd.	4	1	3	3	1	
10		76.02	80.25	V minor alt'n in GND with qtz veins	1	1	1	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 25 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Selvages Alteration	Selvages (0-5)	Ox. State 0-5	% of VEIN & DISSEMINATED MATERIAL: Sulphides pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation oxide	scordite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	1	1.0	1.5	20		1.0	q	3	2	5.0								5.0				B381921	45.72	47.24	**0.023**			VA05060237	1.52
2	1	1.0	1.5	20		1.0	q	3	2	5.0								5.0				B381922	45.72	47.24	**0.013**	DUP		VA05060237	1.52
3	1	1.0	2.5	60		0.5	q	3	3	0.1								5.0				B381923	47.24	48.77	**0.201**			VA05060237	1.53
2	1	3.0	5.0	50		3.0	q	3	2						5.0			5.0				B381924	48.77	49.76	**0.033**			VA05060237	0.99
0																						B381925	49.76	50.29	**<0.005**			VA05060237	0.53
4	1	0.4	1.6	40		1.0	q	3	1				10.0									B381926	50.29	51.82	**0.181**		E.O.H. June 25 (abandoned due to encroaching fire)	VA05060237	1.53
3	1	1.0	3.0	25	50	0.5	q/cb	3	1				1.0						3.0			B382157	51.82	53.34	**0.114**		grey qtz	VA05060971	1.52
1	3	0.7	0.7	40		2.0	q/cb	3	0				2.0																
6	1	1.1	4.5	40	15	5.0	q/chl	3	0	8.0		3.0	1.0						1.0			B382158	53.34	54.86	**0.499**			VA05060971	1.52
							cb	1																					
2	3	0.5	0.8				cb	3	1																				
3	1	1.0	3.0	30		0.0				2.0			0.1					5.0				B382159	54.86	55.55	**0.143**		carb vein areas all broken up - no angles	VA05060971	0.69
2	4	0.2	0.4	45		2.0	cb	2	2				10.0						4.0			B382160	55.55	56.34	**0.266**		lots of bt assc. w/ veins	VA05060971	0.79
4	1	6.0	9.5	60		2.0	q	3	2	2.0								5.0				B382161	56.34	57.91	**2.120**			VA05060971	1.57
1	3	0.4	0.4	70									2.0																
4	1	6.0	9.5	60		2.0	q	3	2	2.0								5.0				B382162	56.34	57.91	**2.300**	DUP		VA05060971	1.57
1	3	0.4	0.4	70									2.0																
3	1	2.0	5.0	45		2.0	q/chl	3	1				12.0						2.0			B382163	57.91	59.44	**0.464**			VA05060971	1.53
3	1	2.5	4.5	50		2.0	q/cb	3	1				10.0						1.0			B382164	59.44	60.96	**0.206**			VA05060971	1.52
1	3	1.0	1.0	150		0.0				2.0								5.0									carb crosscuts qtz vein		
4	1	0.5	2.0	30	40	4.0	q/cb	3	2	6.0			2.0					4.0	1.0			B382165	60.96	62.48	**0.113**			VA05060971	1.52
							chl	1																					
1	1	1.0	1.0	50		0.0				3.0			2.0					5.0	2.0			B382166	62.48	63.55	**0.027**			VA05060971	1.07
1	1	1.0	1.0	20		1.0	q	1	2				10.0						2.0			B382167	63.55	64.01	**0.119**			VA05060971	0.46
2	1	0.3	0.6	30	120	1.0	q	2	0	1.0			2.0									B382168	64.01	65.53	**0.116**			VA05060971	1.52
1	3	0.3	0.3	30		1.0	q/cb	3	2				10.0						3.0										
2	1	0.3	0.6	30	120	1.0	q	2	0	1.0			2.0									B382169	64.01	65.53	**0.093**	PD/CA		VA05060971	1.52
1	3	0.3	0.3	30		1.0	q/cb	3	2				10.0						3.0										
																						B382170	STANDARD 4D		**0.189**	4D		VA05060971	
5	1	1.5	4.0	25	155		q	3					8.0						4.0			B382171	65.53	67.06	**0.007**			VA05060971	1.53
							cb/chl	1																					
8	1	1.0	6.0	30	150	2.0	q	3	2	5.0			5.0					5.0	4.0			B382172	67.06	68.58	**0.044**			VA05060971	1.52
1	1	1.0	1.0	60		1.0	q	2	1				5.0						1.0			B382173	68.58	69.32	**0.005**			VA05060971	0.74
3	1	5.0	8.0	35	70																	B382174	69.32	70.25	**0.196**			VA05060971	0.93
1	1	0.5	0.5	55		1.0	q	4	2				5.0						2.0										
0																						B382175	70.25	71.00	**0.024**			VA05060971	0.75
																						B382176	BLANK		**<0.005**			VA05060971	
1	1	2.0	2.0	30		3.0	q	2	1				20.0						2.0			B382177	71.00	71.94	**0.040**			VA05060971	0.94
1	1	10.0	10.0	140																									
7	1	3.0	7.0	50	30	3.0	q	3	1		9.0		15.0						4.0			B382178	71.94	73.15	**0.122**			VA05060971	1.21
							chl	1																					
4	1	1.0	3.0	30	130	1.0	q	3	1				15.0						3.0			B382179	73.15	74.68	**0.057**			VA05060971	1.53
							cb	1																					
3	4	0.2	0.6	25	40	10.0	cb	2	0				40.0						3.0										
2	1	0.3	0.6	35		1.0	q/cb	3					40.0						5.0			B382180	74.68	75.49	**0.104**			VA05060971	0.81
3	1	1.5	2.5	45		45.0	q/chl	4	4				2.0						4.0			B382181	75.49	76.02	**0.124**			VA05060971	0.53
							cb/s	2																					
3	1	1.5	2.5	45		45.0	q/chl	4	4				2.0						4.0			B382182	75.49	76.02	**0.146**	DUP		VA05060971	0.53
6	1	3.0	9.0	40	140	2.0	q	3			4.0		15.0						3.0			B382183	76.02	77.72	**0.160**		only one vein at 140° (overprinted by one at 40°)	VA05060971	1.70
							cb/chl	1	1																				
1	1	0.8	0.8	30		4.0	q/chl	2					10.0						3.0			B382184	77.72	79.25	**0.621**			VA05060971	1.53
							cb	1	1																				
3	3	0.2	0.6	45		1.0	q/chl	2			3.0																		
							cb	1	1																				
6	1	2.5	6.5	15	35	6.0	q/chl	2					25.0						2.0			B382185	79.25	80.25	**0.804**		ox'n in selvages assc. w/ carb	VA05060971	1.00

DRILL LOG LEGEND P1	DATE: June 26 to July 16, 2006	PAGE 5 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		80.25	82.18	Mod'ly to highly alt'd GND. Broken up and alt'd to clayey to coarse sand texture. Carb veins parallel to CA have slickensides in ser and carb.	3	2	2	2	2	
10		82.18	83.96	Mod alt'd GND around veins. From 83.5 to 83.82m, core is bleached, crumbly white around dark grey sulphide veins	2	1		1	1	
10		83.96	89.11	Unalt'd GND. Straight qtz veins with small silicified selvages.						
10		89.11	90.32	Abrupt change (due to recovery loss?) to bleached, clay-rich extremely alt'd GND. Colour is pale grey - white w/ lenses of ox'd sulphides up to 0.7cm wide. GND texture erased. Soft and crumbly.	1	2	3	3	3	
					0	1	2	0	1	
10		90.32	91.44	Competent hard rock. Silicified GND separated by chl-rich selvages around qtz veins.						
10		91.44	94.93	Same as previous but veinlets of carbonate more prevalent, up to 20 per metre in random orientations, in irregular lines	1	1	2	2	2	
10		94.93	115.82	Highly to extremely alt'd GND. Ser + chl +cb alt'n overprints original GND texture. Colour pale greenish white. Ox'd py in veinlets to veins, usually at 0-25° to CA. Qtz veins visible in places, but generally overprinted by alt'n. 80% competent rock, 20% clay texture (carb + ser). At 106.45m, slickensides in ser and carb on vein face at 0° to CA. Slickens @50° to CA on face.	1	3	3	3	3	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: June 25 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							cb	2	1																				
5	1	1.5	4.5	60	140	1.0	q	2														B382186	80.25	80.77	0.565			VA05060971	0.52
							chl/cb	1	1																				
6	1	1.5	5.0	30	130	1.0	q	2		2.0	2.0		8.0					5.0	3.0			B382187	80.77	82.18	1.000			VA05060971	1.41
							chl/cb	1	1																				
1	4	1.0	1.0	0		1.0	chl/cb	3		0.1								5.0									carb veins parallel to CA		
							q/s	1,3																					
5	1	1.5	6.0	45	65	2.0	q	3	1	3.0	4.0		5.0						3.0			B382188	82.18	83.50	0.360			VA05060971	1.32
1	4	0.5	0.5	0		0.5	cb	3	3																				
5	1	1.5	6.0	45	65	2.0	q	3	1	3.0	4.0		5.0						3.0			B382189	82.18	83.50	0.376	PD/CA		VA05060971	1.32
1	4	0.5	0.5	0		0.5	cb	3	3																				
																						B382190	STANDARD 5E		1.490	5E		VA05060971	
4	6	1.0	2.5	75		30.0	cb/q	5	2	60.0								5.0				B382191	83.50	83.96	0.265		py is ox'd and v. f-grained	VA05060971	0.46
							k	5																					
2	1	1.0	1.4	25	45	4.0	q	3			10.0		4.0						1.0			B382192	83.96	85.34	0.270			VA05060971	1.38
							chl	1																					
5	1	1.0	3.5	40	10	1.0	q	3			10.0		4.0						2.0			B382193	85.34	86.87	0.812			VA05060971	1.53
							chl	1																					
7	1	1.5	6.0	40	60	3.0	q	1		1.0	6.0		12.0						3.0			B382194	86.87	88.39	0.320			VA05060971	1.52
							chl	2																					
2	1	0.6	1.0	20	40	1.0	q	3			4.0											B382195	88.39	89.11	0.036			VA05060971	0.72
																						B382196	BLANK		<0.005			VA05060971	
5	6	0.7	2.0	60		121.0	s/chl	3	1	100.0								5.0				B382197	89.11	90.32	0.256		ox'd clay sulphides	VA05060971	1.21
							cb	4																					
6	1	1.0	5.0	40	60	5.0	q/chl	4					3.0									B382198	90.32	91.44	0.138			VA05060971	1.12
							s/cb	1																					
2	4	0.5	1.0	40		10.0	q/chl	4		60.0			10.0					4.0											
							cb/s	2	1																				
5	1	2.0	7.0	70	120	4.0	q/chl	4		10.0			2.0					2.0				B382199	91.44	92.96	0.097			VA05060971	1.52
							cb	2																					
2	4	0.2	0.4	45	15	0.0																							
6	1	2.5	9.0	50		20.0	q/chl	4			3.0		9.0									B382200	92.96	94.49	0.140			VA05060971	1.53
5	4	0.5	1.5	20	75		cb/s	2																					
5	6	0.2	1.0	80	100	44.0	q/chl	3	1	80.0								3.0				B382201	94.49	94.93	0.222			VA05060971	0.44
							s/cb	3																					
5	6	0.2	1.0	80	100	44.0	q/chl	3	1	80.0								3.0				B382202	94.49	94.93	0.306	DUP		VA05060971	0.44
2	1	1.0	2.0	60		50.0	chl/s	4		3.0			3.0					5.0				B382203	94.93	96.01	0.081		selvage for both vein types	VA05060971	1.08
							cb/q	2																					
2	3	1.0	2.0	40	70					3.0			3.0																
4	1	1.0	4.0	40			s/chl	4														B382204	96.01	97.54	0.119		selvage extends beyond sample boundaries	VA05060971	1.53
							cb/q	3																					
1	6	0.5	0.5	35						90.0								4.0											
9	1	1.0	5.0	40			s/chl	4		5.0			2.0					3.0				B382205	97.54	99.06	0.245			VA05060971	1.52
							cb/q	3																					
1	6	1.0	1.0	40			q/cb	4		60.0								4.0											
							s/chl	4																					
3	1	1.0	2.0	40	60		chl/q	4	0	2.0			8.0					5.0	1.0			B382206	99.06	100.58	0.105		whole section alt'd selvage	VA05060971	1.52
							s/cb	3																					
3	6	0.2	0.6	10	20		chl/q	4		100.0								5.0				B392207	100.58	102.11	0.164		ox'd clay py	VA05060971	1.53
							s/cb	3																					
2	3	0.5	1.0	15			chl/q	4		5.0			5.0					5.0	3.0			B392208	102.11	103.63	0.122			VA05060971	1.52
							s/cb	3																					
2	3	0.5	1.0	15			chl/q	4		5.0			5.0					5.0	3.0			B392209	102.11	103.63	0.110	PD/CA		VA05060971	1.52
																						B392210	STANDARD 2B		2.870	2B		VA05060971	
3	3	0.5	1.5	20			chl/q	4		10.0			6.0					5.0				B382211	103.63	105.16	0.539			VA05060971	1.53
							s/cb	3																					
2	6	0.2	0.4	0	30		chl/q	4		90.0								5.0									10% carb		
							s/cb	3																					
3	4	0.4	0.2	0	20		chl/q	4		40.0								5.0				B382212	105.16	106.68	0.065			VA05060971	1.52
							s/cb	3																					
2	1	1.0	2.0	30	40					3.0	2.0		5.0					5.0											
4	6	0.4	1.2	20	40		chl/q	4		100.0								4.0				B382213	106.68	107.57	0.045			VA05060971	0.89

DRILL HOLE # : DG05-291C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		115.82	123.44	Minor alt'd GND. Broken up due to carb-infusion from 115.82 to 117.05m. 95% unalt'd GND. Silicified and chl'd qtz vein selvages are the only alt'n besides minor carb veining through rest of section (below 117.05m).	0	0	1	1	1	
10		123.44	125.61	Carb-infused GND. Veinlets and throughout matrix of GND causes rock to be soft and crumbly			1	2	3	
10		125.61	129.84	Back to unalt'd GND. Sheeted qtz veins with silicified/ chloritized selvages. Late calcite with qtz is up to 20% of veins.			1		2	
10		129.84	131.16	Chloritized and carb'd coherent rocks.		1	3	1	2	
10		131.16	134.56	Unalt'd GND w/ sheeted qtz veins. At 134.11m, slickensides on fract face at 45° to CA, in ser +carb+chl+ox'd py (soft clay material).		1	1		1	
10		134.53	139.38	Increased carbonate content (up to ~10% of section) causes rock to appear somewhat bleached. Texture soft and easily broken, crumbly over 40%. Qtz veins continue, selvages with ser + chl still visible, silicified sections more competent than non-sil.		1	1	1	2	
10		139.38	144.78	Highly alt'd GND, w/ carb becoming pervasive in some sections up to 40cm long. Rock is carb-clay soft and crumbly. Chl also intense. Colour med greenish grey.		1	2	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 25 to July 16, 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Selvages Alteration	Selvages (0-5)	Ox. State 0-5	% of VEIN & DISSEMINATED MATERIAL: Sulphides pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation oxide	scordite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							s/cb	3																					
1	3	1.0	1.0	65			chl/q	4		5.0								5.0											
							s/cb	3																					
2	6	0.4	0.8	65						100.0								3.0				B382214	107.57	108.20	0.052		py less ox'd	VA05060971	0.63
2	6	0.3	0.6	35	5					90.0								4.0				B382215	108.20	109.73	0.083			VA05060971	1.53
1	1	0.8	0.8	45						5.0								5.0											
																						B382216	BLANK		<0.005			VA05060971	
5	6	1.0	2.2	10	60					90.0								4.0				B382217	109.73	111.25	0.250			VA05060214	1.52
3	3	1.0	2.0	35						15.0								4.0											
6	4	0.5	1.8	20	40					50.0								5.0				B382218	111.25	112.78	0.059			VA05060214	1.53
1	6	0.5	0.5	50						100.0								5.0											
4	1	1.0	4.0	45						5.0								4.0				B382219	112.78	114.30	0.173			VA05060214	1.52
2	4	2.0	4.0	40						3.0			2.0					5.0											
12	3	0.5	5.0	30	50					10.0	0.1							5.0				B382220	114.30	115.82	0.218			VA05060214	1.52
1	6	0.3	0.3	30						100.0								5.0											
5	1	2.0	7.0	30		1.0	q/chl	3		100.0								5.0				B382221	115.82	117.35	0.146			VA05060214	1.53
4	4	1.0	2.2	30	5					10.0								5.0											
5	1	2.0	7.0	30		1.0	q/chl	3		100.0								5.0				B382222	115.82	117.35	0.047	DUP		VA05060214	1.53
4	4	1.0	2.2	30	5					10.0								5.0											
3	1	1.0	3.0	40	50	2.0	q/chl	3	0		5.0		5.0						2.0			B382223	117.35	118.87	0.089			VA05060214	1.52
6	3	0.2	1.2	10	30																								
5	1	1.0	4.0	50		1.0	q/chl	3	0	2.0	0.1		2.0					4.0	1.0			B382224	118.87	120.40	0.086			VA05060214	1.53
1	6	0.3	0.3	60		4.0	q/chl	4,1	0		5.0		70.0																
7	1	1.0	4.0	60		2.0	q/chl	3,2			2.0		10.0						2.0			B392225	120.40	121.92	0.084			VA05060214	1.52
11	1	2.0	9.0	45		2.0	q/chl	3,1	0		5.0		10.0						2.0			B392226	121.92	123.44	0.072			VA05060214	1.52
4	1	1.5	3.5	45		1.0	q/chl	3,1	0				5.0						4.0			B392227	123.44	124.97	0.123			VA05060214	1.53
1	1	1.0	1.0	30		1.0	q/chl	3,1					3.0						3.0			B382228	124.97	125.61	0.016			VA05060214	0.64
1	1	1.0	1.0	30		1.0	q/chl	3,1					3.0						3.0			B382229	124.97	125.61	0.102	PD/CA		VA05060214	0.64
																						B382230	STANDARD 6F		2.900	6F		VA05060214	
3	1	0.6	1.4	40		2.0	q/chl	3,2	0		2.0		5.0						3.0			B382231	125.61	126.49	0.275			VA05060214	0.88
7	1	1.0	5.0	35	140	2.0	q/chl	3	0		2.0		5.0						3.0			B382232	126.49	127.28	0.292			VA05060214	0.79
8	1	0.5	4.0	40		2.5	q/chl	3			3.0		8.0						3.0			B382233	127.28	128.02	0.099			VA05060214	0.74
							cb	2																					
8	1	0.5	4.0	40		2.0	q/chl	3			6.0		8.0						4.0			B382234	128.02	128.77	1.990			VA05060214	0.75
							cb	2																					
6	1	0.5	2.0	45		2.0	q/chl	3			8.0		10.0						4.0			B382235	128.77	129.54	0.477			VA05060214	0.77
							cb	2																					
																						B382236	BLANK		<0.005			VA05060214	
2	1	0.4	0.7	50		2.0	q/chl	3					3.0						3.0			B382237	129.54	129.84	0.366			VA05060214	0.30
							cb	2																					
4	1	1.3	3.0	40		150.0	q/chl	4		3.0			5.0	0.1					1.0			B382238	129.84	131.16	0.111		selvage for all veins = 1 sample	VA05060214	1.32
							cb	3																					
12	1	1.0	7.0	45	30	2.0	q	4	0	1.0	8.0		6.0						2.0			B382239	131.16	132.59	0.097			VA05060214	1.43
							chl/cb	1																					
11	1	2.0	10.0	50	35	4.0	q	4		1.0	3.0		6.0						1.0			B382240	132.59	133.34	0.521			VA05060214	0.75
							chl/cb	3,2																					
5	1	2.0	6.5	50	35	8.0	q/chl	3			5.0		2.0						3.0			B382241	133.34	134.11	0.127			VA05060214	0.77
							cb	2																					
5	1	2.0	6.5	50	35	8.0	q/chl	3			5.0		2.0						3.0			B382242	133.34	134.11	0.119	DUP		VA05060214	0.77
6	1	1.0	2.5	40	10	1.0	q/chl	3			5.0		5.0						2.0			B382243	134.11	134.53	0.143			VA05060214	0.42
							cb	2																					
3	1	2.0	5.0	50		1.0	q/chl	2			1.0		10.0						2.0			B382244	134.53	135.63	0.087		20 carb veinlets per metre	VA05060214	1.10
3	4	0.5	1.5	65	40																								
3	1	1.0	3.0	50		1.0	q/chl	2		1.0			8.0									B382245	135.63	136.39	0.100			VA05060214	0.76
1	6	0.5	0.5	65						90.0	1.0							2.0											
2	1	1.0	2.0	50		2.0	q/chl	3		1.0			10.0					5.0	2.0			B382246	136.39	137.30	0.062			VA05060214	0.91
5	4	0.2	1.0	40		1.0	cb	2																					
9	1	2.5	6.5	40	50	2.0	q/chl	4		4.0			5.0					5.0	2.0			B382247	137.30	138.68	1.375			VA05060214	1.38
3	1	1.0	2.6	50	35	1.0	q/chl	3			2.0		10.0						3.0			B382248	138.68	139.38	0.093			VA05060214	0.70
							cb	1																					
3	1	1.0	2.6	50	35	1.0	q/chl	3			2.0		10.0						3.0			B382249	138.68	139.38	0.076	PD/CA		VA05060214	0.70
																						B382250	STANDARD 7G		4.470	7G		VA05060214	
1	3	3.0	3.0	65		40.0	q/chl	2		4.0								5.0				B382251	139.38	140.21	0.322		v. crumbly and soft	VA05060214	0.83

DRILL LOG LEGEND P1 | DATE: June 26 to July 16, 2005 | PAGE 1 of 16

DRILL HOLE # : DG05-291C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		144.78	156.97	GND, alt'd only around qtz veins (selvages). Sheeted veins at 50° to CA.		1	1		1	
10		156.97	170.69	GND w/ approx 6 qtz veins per metre and 15 carb veinlets per metre of core. Outside selvages and carb'd (crumbly) sections, rock is unalt'd. Colour med grey.		1	1		1	
10		170.69	173.74	Sheeted qtz veins continue through more carb-rich zone. Veinlets of powdery, opaque white carbonate are at 60° and 10° to CA and cause rock to crumble.		1	1		2	
10		173.74	178.31	Selvages dominate core (section is 70% minorly alt'd w/ ser and chl). Less carb means more competent rock. Slickensides on faces at 40° in ser, chl.		2	2		1	
10		178.31	182.88	80% unalt'd GND. 30cm zone of carb-rich. 30cm chloritic selvage around 3 1cm qtz veins. All competent. Slickensides in ox'd and unox'd py on face at 30° to CA.		1	1		1	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 26 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

#/meter	Type	VEINS Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Alteration	(0-5)	Ox. State 0-5	% of VEIN & DISSEMINATED MATERIAL Sulphides pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation oxide	scordite	biotite	other	Sample Number	Interval From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							cb/s	3																					
5	1	1.0	5.0	40	110	6.0	q/chl	3					3.0						2.0			B382252	140.21	141.73	0.257			VA05060214	1.52
							cb/s	2																					
3	4	0.6	1.8	30	10	10.0	cb	3		3.0								5.0											
5	1	1.2	3.0	25	40	3.0	q/chl	2		2.0		1.0	5.0					4.0	2.0			B382253	141.73	143.26	0.176			VA05060214	1.53
							cb/s	2																					
6	4	0.5	2.0	140	110	2.0	cb	1		10.0								5.0											
4	1	1.0	4.0	50		2.0	q/chl	3		2.0			4.0					3.0	3.0			B382254	143.26	144.78	0.063			VA05060214	1.52
							cb/s	2																					
8	1	1.0	8.0	40	25	2.0	q/chl	4	2	2.0	4.0		8.0						3.0			B382255	144.78	146.30	0.172			VA05060214	1.52
																						B382256	BLANK		<0.005			VA05060214	
9	1	1.5	7.0	45	25	6.0	q/chl	3		1.0	7.0		10.0						2.0			B382257	146.30	147.83	0.060			VA05060214	1.53
							cb	2																					
1	3	1.0	1.0	35		1.5	q/cb	3					15.0						2.0										
							chl	3																					
4	1	2.0	5.0	30	40	2.0	q/chl	4					20.0						1.0			B382258	147.83	148.60	7.760			VA05060214	0.77
							cb	2																					
4	1	3.0	8.0	35		14.0	q/chl	4			5.0		10.0						2.0			B382259	148.60	149.39	0.105			VA05060214	0.79
1	1	1.5	5.0	40		10.0	q/chl	4			3.0		10.0						3.0			B382260	149.39	150.88	0.938			VA05060214	1.49
							cb	1																					
9	1	1.0	7.0	40	35	4.0	q/chl	4			8.0	1.0						1.0				B382261	150.88	152.40	0.200			VA05060214	1.52
							cb	1																					
9	1	1.0	7.0	40	35	4.0	q/chl	4			8.0	1.0						1.0				B382262	150.88	152.40	0.323	DUP		VA05060214	1.52
5	1	1.0	5.0	45		2.0	q/chl	4		2.0	3.0		5.0						1.0			B382263	152.40	153.92	0.391			VA05060214	1.52
							cb	1																					
2	3	1.0	2.0	45	25	1.0	cb	4																					
8	1	2.5	6.0	40	60	3.0	q/chl	4			2.0		4.0									B382264	153.92	155.45	0.080			VA05060214	1.53
1	4	10.0	10.0	55		20.0	chl/cb	4		10.0								5.0											
10	1	1.2	10.0	40	60	10.0	q/chl	3		3.0	1.0		8.0						1.0			B382265	155.45	156.97	0.122			VA05060214	1.52
							cb	2																					
6	1	2.0	5.0	10	30	1.0	q/chl	3				1.0	10.0						2.0			B382266	156.97	158.50	0.071			VA05060214	1.53
							cb	1																					
1	4	3.0	3.0	70		26.0	chl/cb	4					0.1																
							q/s	2																					
5	1	2.5	6.0	40		5.0	q/chl	4			2.0		7.0						2.0			B382267	158.50	160.02	0.086			VA05060214	1.52
3	4	0.3	0.9			20.0	cb/s	3																					
							chl	3																					
8	1	3.0	12.0	40		2.0	q/chl	3			5.0		5.0						1.0			B382268	160.02	161.54	0.060			VA05060214	1.52
8	1	3.0	12.0	40		2.0	q/chl	3			5.0		5.0						1.0			B382269	160.02	161.54	0.080	PD/CA		VA05060214	1.52
																						B392270	STANDARD 3C		0.094	3C		VA05060214	
4	3	0.6	1.5	30		2.0	q/chl	3			5.0		5.0						1.0			B392271	161.54	163.07	0.189		aspy slickensides	VA05060214	1.53
							cb	2																					
3	3	1.0	3.0	45		4.0	q/chl	4			8.0		5.0						1.0			B382272	163.07	164.59	0.122			VA05060214	1.52
2	6	0.5	1.0	30		20.0	cb	4	1	60.0								4.0											
							chl	3																					
8	1	1.5	8.0	40	50	1.0	q	3			8.0		5.0						3.0			B382273	164.59	166.12	0.236			VA05060214	1.53
9	1	1.0	5.0	50		1.0	q	4			8.0		5.0						3.0			B382274	166.12	167.64	0.052			VA05060214	1.52
9	1	1.5	6.5	30	45	1.0	q	4			3.0		2.0						3.0			B382275	167.64	169.16	0.197			VA05060214	1.52
							cb	1																					
																						B382276	BLANK		<0.005			VA05060214	
6	1	1.0	4.0	35	70	1.0	q/chl	3			5.0		8.0						3.0			B382277	169.16	170.69	0.044			VA05060214	1.53
5	1	1.0	4.0	40	55	2.0	q/chl	3			10.0		5.0						3.0			B382278	170.69	171.59	0.509			VA05060214	0.90
3	1	1.5	3.5	40		1.0	q	3			10.0											B382279	171.59	172.21	0.129			VA05060214	0.62
8	1	2.0	10.0	45		1.5	q	3			10.0		5.0						1.0			B382280	172.21	173.74	0.231			VA05060214	1.53
							chl	1																					
6	4	0.2	1.2	60	10	0.5	cb	4																					
3	1	2.0	5.0	35		3.0	q/chl	3		3.0	6.0		6.0						3.0			B382281	173.74	175.26	0.052			VA05060214	1.52
3	1	2.0	5.0	35		3.0	q/chl	3		3.0	6.0		6.0						3.0			B382282	173.74	175.26	0.154	DUP		VA05060214	1.52
7	1	5.0	11.0	40	130	4.0	q/chl	3			12.0		6.0						2.0			B382283	175.26	176.78	0.118			VA05060214	1.52
							s/cb	1																					
7	1	1.0	6.0	20	130	12.0	q/chl	4			4.0		5.0						3.0			B382284	176.78	178.31	0.064			VA05060214	1.53
							s/cb	1																					
1	4	0.2	0.2	70		20.0	cb/chl	3		20.0	5.0		5.0					4.0	3.0										
							q/s	3																					
9	1	1.0	7.0	40		3.0	q	3					8.0						3.0			B382285	178.31	179.83	0.397			VA05060214	1.52
5	1	1.0	5.0	40	70	2.0	q	3			2.0		10.0						2.0			B382286	179.83	181.36	0.025			VA05060214	1.53

DRILL LOG LEGEND P1	DATE: June 26 to July 16, 2006	PAGE 11 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		182.88	185.93	Another carb-rich zone. White, crumbly carb in veinlets and throughout matrix of GND overprints qtz veins. Some chl'd selvages still visible.		1	1	1	2	
10		185.93	188.98	Mod'ly alt'd GND. Minor carb in veinlets and through 50% of matrix. Qtz veins have silicified and chl'd selvages twice as wide as the veins themselves.	0	2	1	1	2	
10		188.98	192.02	GND texture is 95% erased to aphanitic chloritic/sericitic competent core. One 5cm qtz vein at 196.60m. Colour is medium greyish green, minor veinlets of carbonate overprint rock at low angles (<20° to CA)						
10		192.02	193.55	Highly alt'd GND. Carb (white, powdery) in veinlets and through matrix of GND. Texture crumbly over 60% of section. Competent core up to 15cm long.	1	2	2	2	3	
10		193.55	202.89	Minor to mod alt'n through section, depending on carb infusion amount, sections up to 30cm of mod alt'n. Silicified and chl'd selvages are small around qtz veins.		1	1		1	
10		202.89	204.75	V little carb; qtz veins w/ chl'd selvages interrupt unalt'd GND.		1	1			
10		204.75	208.22	GND infused w/ carb, so crumbly and broken. Sheeted qtz veins continue.		1	1		3	
10		208.22	212.73	Moderate carb alt'n overprints qtz veins and their sil'd, chl'd selvages. At 212.40m, 30cm section of sub-rounded, lim-covered cobbles, ave size 5cm; may be due to late brittle faulting and motion, with influx of lim-rich meteoric waters, or surface waters infiltrating rock and weathering it.	1	1	1	1	2	
10		212.73	216.41	Remnant qtz vein pieces within carb-rich GND. Coherent core (70%) appears sheared, hence the vein destruction. Sulphides in veinlets throughout section.	1	1		2	3	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 25 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL:														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other		From	To					
8	1	2.0	7.0	40	150	30.0	q/chl	5		15.0			12.0					3.0	3.0			B382287	181.36	182.88	0.037			VA05060214	1.52
4	1	3.0	5.0	40	70	4.0	q/chl	3		1.0	1.0		10.0						3.0			B382288	182.88	184.40	0.030			VA05060214	1.52
							s/cb	2																					
4	1	3.0	5.0	40	70	4.0	q/chl	3		1.0	1.0		10.0						3.0			B382289	182.88	184.40	0.053	PD/CA		VA05060214	1.52
																						B382290	STANDARD 2B		3.050	2B		VA05060214	
4	1	1.0	3.0	40		1.0	q/chl	3			5.0	1.0	8.0						1.0			B382291	184.40	185.93	0.138			VA05060214	1.53
7	4	0.3	2.0	0	60	4.0	cb	3																					
7	1	2.0	5.0	45	120	4.0	q/chl	3			10.0		5.0						2.0			B382292	185.93	187.45	0.079			VA05060214	1.52
							cb/s	1																					
4	1	2.0	4.0	45	35	2.0	q/cb	3			14.0	2.0	5.0						4.0			B382293	187.45	188.98	0.125			VA05060214	1.53
							chl	1																					
1	4	0.7	0.7	150		4.0	cb/chl	4	1																				
							q	1																					
2	1	1.4	2.4	45		8.0	q/chl	4	1	30.0								1.0				B382294	188.98	190.50	0.053			VA05060214	1.52
							cb	2																					
2	1	5.0	7.0	50		50.0	q/chl	4	1		6.0		10.0						3.0			B382295	190.50	192.02	0.091			VA05060214	1.52
							cb	3																					
6	4	1.0	5.0	55	70	20.0	cb	4		10.0								5.0												
																						B382296	BLANK		<0.005			VA05060214	
8	1	1.0	6.5	50		50.0	q/chl	4														B382297	192.02	193.55	0.170			VA05060214	1.53
							cb	3																					
3	4	1.0	2.0	50		20.0	cb	4		10.0								5.0												
																						B382298	193.55	194.35	0.105			VA05060214	0.80
7	1	2.0	7.4	30	130	6.0	q/chl	4			4.0		15.0						1.0			B382299	194.35	195.07	0.245			VA05060214	0.72
1	4	1.0	1.0	60		20.0	chl/cb	4		10.0								5.0												
8	1	2.5	8.6	50	60	6.0	q/chl	4		15.0	2.0		10.0					2.0	2.0			B382300	195.07	195.74	0.283			VA05060214	0.67
							cb	3																					
9	1	1.5	10.0	70	110	2.0	q/cb	2					20.0									B382301	195.74	196.60	0.078			VA05060214	0.86
1	3	1.0	1.0	90		12.0	cb	2																					
9	1	1.5	10.0	70	110	2.0	q/cb	2					20.0									B392302	195.74	196.60	0.116	DUP		VA05060214	0.86
1	3	1.0	1.0	90		12.0	cb	2																					
5	1	3.0	12.0	50	30	4.0	q/cb	4			10.0		2.0					1.0				B382303	196.60	198.12	0.224			VA05060214	1.52
							chl	2																					
3	1	1.2	3.0	55	35	2.0	q/chl	3			6.0		2.0					3.0	1.0			B382304	198.12	199.64	0.359			VA05060214	1.52
							cb	3																					
6	1	1.0	4.5	60	40	1.0	q	3			8.0		20.0					2.0	1.0			B392305	199.64	201.17	0.092			VA05060214	1.53
2	4	1.0	1.3	0	30	12.0	cb	3					3.0						4.0											
							chl	2																					
1	1	1.0	1.0	50		0.5	q/chl	1														B392306	201.17	202.09	0.104			VA05060214	0.92
2	4	1.0	1.0	30	130	26.0	cb/chl	4		13.0								3.0												
1	1	1.0	1.0	30		3.0	q/chl	2			10.0		5.0					1.0	2.0			B382307	202.09	202.89	0.099			VA05060214	0.80
1	6	0.4	0.4	45		2.0	cb/chl	3		70.0								4.0												
							q	1																					
8	1	2.0	6.0	40	150	18.0	q/chl	4			12.0		2.0					1.0	1.0			B382308	202.89	203.78	0.065			VA05060214	0.89
							cb/s	2																					
8	1	2.0	6.0	40	150	18.0	q/chl	4			12.0		2.0					1.0	1.0			B382309	202.89	203.78	0.066	PD/CA		VA05060214	0.89
																						B382310	STANDARD 4D		0.424	4D		VA05060214	
6	1	2.0	8.0	40	10	3.0	q/chl	3			9.0		5.0					1.0	2.0			B382311	203.78	204.22	0.278			VA05060214	0.44
3	1	2.0	4.0	45		2.0	q/chl	3			10.0		5.0					1.0	3.0			B382312	204.22	204.75	0.113			VA05060214	0.53
7	1	1.2	5.5	50	40	1.0	q/cb	4			5.0		10.0						3.0			B382313	204.75	205.74	0.106			VA05060214	0.99
10	1	1.0	7.0	40	20	3.0	q/chl	3			15.0	3.0	10.0					1.0	4.0			B382314	205.74	207.26	0.045			VA05060214	1.52
							cb/s	2																					
2	1	4.0	5.0	50		2.0	q/chl	3			20.0											B382315	207.26	208.22	0.029			VA05060214	0.96
							cb/s	1																					
																						B382316	BLANK		<0.005			VA05060214	
4	1	1.0	3.5	45	65	8.0	q/cb	4			20.0	1.0										B382317	208.22	208.79	0.132			VA05060214	0.57
							chl/s	1																					
7	1	1.0	7.0	50	25	1.0	q	2			15.0											B382318	208.79	210.31	0.066			VA05060214	1.52
7	1	1.5	5.5	60	25	1.0	q/chl	3,1			15.0		2.0									B382319	210.31	211.84	0.093			VA05060214	1.53
3	1	4.0	7.0	45		1.0	q	3	2													B382320	211.84	212.73	0.136			VA05060214	0.89
2	1	1.0	2.0	45		1.0	q	3			0.1											B382321	212.73	213.36	0.083			VA05060214	0.63
2	1	1.0	2.0	45		1.0	q	3			0.1											B382322	212.73	213.36	0.133	DUP		VA05060214	0.63

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2006	PAGE 13 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		216.41	219.03	Veins now unsheared, selvages still present beneath moderate carb alt'n.	2	3	1	2	2	
10		219.03	219.46	Dark grey aphanitic, silicified GND. Dark grey to black clay and carb on fracture faces. Grades into next section...		1	1	2	1	
10		219.46	220.43	Ser/chl/carb alt'n, moderate. GND texture 50% erased to pale whitish green colour.		2	3	1	3	
10		220.43	228.60	Unalt'd GND w/ sheeted qtz veins continuing but with less defined margins - has been 'reheated' or cooled more slowly here than up in hole. Also far less carbonate here; rock is solid. Straight fractures in random orientations. At 221.35m, qtz vein contains ~20% py and has obviously been offset along late sulphide veinlets.		1	1		1	
10		228.60	231.52	Sulphide veins begin, with large selvages of chl, ser (+minor carb) alt'n.	1	2	2			1
10		231.52	223.17	Carbonate content increases so rock is v broken up into lengths less than 10cm.	1	2	2	1	2	
10		233.17	240.09	V minor silicification and chloritization of GND around qtz veins, which are fewer but larger. One 12.5cm grey qtz vein at 237.42m. Sulphide veinlets offset qtz veins sinistrally if qtz veins are at 30° and sulph veins are at 160° to CA. Carbonate appears in few veinlets, later than other veinlets/veins. Concentrated (up to 5%) in 30cm length from 237.56 to 237.86m.	1		1		1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 26 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max. (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	1.2	2.2	40		1.0	q/chl	2			6.0		2.0						2.0			B382323	213.36	214.88	0.120			VA05060214	1.52
4	1	5.0	10.0	50		0.0				10.0	8.0		3.0					4.0				B382324	214.88	216.41	0.216		selvages all sheared away	VA05060214	1.53
3	6	0.3	0.7	30						80.0								5.0									only one vein has orig. angle		
5	1	2.0	7.5	50						3.0	10.0		5.0					5.0	4.0			B382325	216.41	217.93	0.170			VA05060214	1.52
1	6	0.7	0.7	30						70.0								4.0											
3	1	1.5	3.5	60	20	1.5	q	3					5.0						3.0			B382326	217.93	219.03	0.103			VA05060214	1.10
							chl	1																					
1	4	1.0	1.0	60		2.0	cb/b	2		15.0								5.0											
3	1	1.0	2.0	10	90																	B382327	219.03	219.46	0.024			VA05060214	0.43
4	1	2.0	5.0	45		1.0	cb/q	3														B382328	219.46	220.43	0.097			VA05060214	0.97
							chl/s	3																					
4	1	2.0	5.0	45		1.0	cb/q	3														B382329	219.46	220.43	0.177	PD/CA		VA05060214	0.97
																						B382330	STANDARD 5E		1.345	5E		VA05060214	
6	1	2.0	8.0	50		1.0	q	4			5.0		3.0					1.0	3.0			B382331	220.43	220.98	0.096			VA05060214	0.55
9	1	3.0	11.0	40		1.0	q	4		10.0	5.0		1.0					2.0	3.0			B382332	220.98	221.59	0.133			VA05060214	0.61
5	1	35.0	10.0	50		1.0	q	2			12.0		2.0						3.0			B382233	221.59	222.50	0.141			VA05060214	0.91
							chl/s	1																					
5	1	5.0	8.0	45	35	2.0	q/chl	3			6.0		4.0						4.0			B382334	222.50	223.26	0.526			VA05062470	0.76
							s	1																					
2	1	1.0	2.0	30		1.0	q	2			3.0		3.0						4.0			B382335	223.26	224.03	0.036			VA05062470	0.77
3	6	0.3	0.9	40	140	10.0	q/chl	4		60.0								2.0											
							s/cb	2														B382336	BLANK		<0.005			VA05062470	
5	1	1.0	2.5	50	60	2.0	q	2	1		10.0											B382337	224.03	224.63	0.062			VA05062470	0.60
6	1	1.5	6.5	40		2.0	q/chl	3			15.0											B382338	224.63	225.55	0.037			VA05062470	0.92
							cb	2																					
10	1	2.0	10.0	45	40	2.0	q	2		2.0	10.0		8.0						2.0			B382339	225.55	227.08	0.083			VA05062470	1.53
6	1	3.0	9.0	50	70	2.0	q	3			2.0		2.0									B382340	227.08	227.80	0.177			VA05062470	0.72
6	1	2.0	6.5	35	70	6.0	q/chl	2			4.0		3.0						2.0			B382341	227.80	228.60	1.790			VA05062470	0.80
6	1	2.0	6.5	35	70	6.0	q/chl	2			4.0		3.0						2.0			B382342	227.80	228.60	0.129	DUP		VA05062470	0.80
4	1	1.0	4.0	40	130	2.0	q/chl	3			2.0		3.0						2.0			B382343	228.60	230.12	0.104			VA05062470	1.52
4	6	0.2	0.8	85		10.0	q/chl	4		80.0								4.0											
							cb/s	3																					
4	1	1.8	3.3	30	40	1.0	q	2			8.0		3.0						4.0			B382344	230.12	231.52	0.213			VA05062470	1.40
							chl/cb	1																					
2	6	0.3	0.6	20		4.0	q/chl	4		60.0	10.0		15.0					4.0	4.0										
							cb/s	2																					
3	1	1.5	4.5	40		1.0	q	2		15.0	5.0	1.0						3.0				B382345	231.52	232.42	0.086			VA05062470	0.90
							cb/chl	2																					
2	4	2.0	3.0	40	45	12.0	cb/chl	4	1	10.0								5.0											
							q/s	2																					
3	1	2.0	5.0	25		50.0	cb/chl	4	1	10.0	5.0		10.0					4.0	3.0			B382346	232.42	233.17	0.068			VA05062470	0.75
							q/s	2																					
4	1	3.0	7.0	35		8.0	q/chl	3			1.0		5.0						4.0			B382347	233.17	234.70	0.083			VA05062470	1.53
							cb/s	1																					
3	6	0.2	0.5	55						80.0								4.0											
4	1	1.0	4.0	60	45					8.0	5.0		2.0					4.0				B382348	234.70	236.22	0.027			VA05062470	1.52
3	6	0.2	0.6	15	50					100.0								5.0											
4	1	1.0	4.0	60	45					8.0	5.0		2.0					4.0				B382349	234.70	236.22	0.032	PD/CA		VA05062470	1.52
3	6	0.2	0.6	15	50					100.0								5.0											
																						B382350	STANDARD 6F		2.660	6F		VA05062470	
5	1	12.5	18.5	30		4.0	q/chl	2		2.0	14.0	3.0	15.0		0.1							B382351	236.22	236.98	3.440			VA05062470	0.76
							cb/s	2																					
5	6	0.2	1.0	160		0.2	chl/cb	4																					
4	1	2.0	5.0	40		2.0	q/chl	2					3.0									B382352	236.98	237.56	0.101			VA05062470	0.58
3	6	0.2	0.6	35	85	0.2	cb/chl	1	1	100.0								5.0											
4	6	0.3	1.0	130		6.0	q/chl	3		97.0		3.0						1.0				B382353	237.56	238.08	0.069			VA05062470	0.52
							cb/s	3																					
2	1	0.5	1.0	60		2.0	q/chl	2					7.0																
3	6	0.2	0.6	0	45	1.0	q/cb	2	2	100.0								5.0				B382354	238.08	239.27	0.105			VA05062470	1.19
							chl/cb	1																					
4	1	3.0	8.0	55	35	1.0	q/chl	2			10.0	1.0	4.0					1.0				B382355	239.27	240.05	0.246			VA05062470	0.78
																						B382356	BLANK		<0.005			VA05062470	

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 15 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		240.09	240.94	Crumbly carb-infused GND. Veinlets and throughout matrix. Coherent core <10cm long. Clay rich. Ox'd py throughout (from old sulph veins).	2	2	2	1	3	
10		240.94	244.56	Fewer qtz veins in unalt'd GND. Sulph veinlets still offsetting qtz veins, as at 233.17 to 240.09m.	1		1		1	
10		244.56	245.36	Crumbly/clay to competent highly alt'd GND. Chlorite and silicification are pervasive and colour is solid greenish grey. Only qtz eyes left of GND texture. Carbonitic clay contacts are at 125° (upper) and 25° (lower).	2	2	3	2	2	
10		245.36	248.41	Minor to mod carb alt'n throughout. Otherwise unalt'd GND w/ continuing qtz veins and sulphide veinlets.	1	1	1	0	2	
10		248.41	259.08	Unalt'd GND w/ sheeted veins, at lower angles (<10°), for first sample, to 249.94m. Mod to strong slickensides on fracture faces. Solid core.			1		1	
10		259.08	266.57	More carb alt'd GND. Texture is granular, somewhat crumbly but overall GND texture preserved, just softened. Sulphide veins more numerous and bigger - up to 0.5cm wide. Fewer qtz veins, somewhat rearranged by weak foliation parallel to carbonate and sulphide veinlets.	1	1	1	2	3	
			E.O.H.							

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 25 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	3.0	3.0			10.0	q/chl	3	2				6.0						4.0			B382357	240.05	240.94	0.109		qtz pieces	VA05062470	0.89
5	1	1.0	4.0	45		1.0	q/cb	2,1	1		9.0		5.0					1.0	1.0			B382358	240.94	241.66	0.120			VA05062470	0.72
4	6	0.2	0.8	40		2.0	q/chl	4	1	80.0		1.0	5.0					5.0										
1	1	4.0	4.0	40		4.0	q/chl	3	1	10.0	5.0		15.0					2.0	0.0			B382359	241.66	242.32	0.129			VA05062470	0.66
							cb/s	1																					
2	6	0.2	0.4	140		2.0	q/chl	4	2	90.0								5.0											
3	1	4.0	6.0	45		4.0	q/chl	3	2		5.0		5.0						4.0			B382360	242.32	242.98	0.087			VA05062470	0.66
							cb/s	1																					
2	6	0.2	0.4	140		1.0	q	3		90.0		5.0						2.0											
5	1	1.5	5.5	45		2.0	q/chl	2	0		3.0		1.0					2.0	5.0			B382361	242.98	243.84	0.059			VA05062470	0.86
							cb/s	1																					
5	1	1.5	5.5	45		2.0	q/chl	2	0		3.0		1.0					2.0	5.0			B382362	242.98	243.84	0.138	DUP		VA05062470	0.86
2	1	1.0	2.0	55	150	3.0	q/chl	2	1		3.0											B382363	243.84	244.56	0.059			VA05062470	0.72
							cb/s	2																					
1	4	4.0	4.0	125		14.5	cb/chl	4	2	30.0								3.0				B382364	244.56	245.36	0.061			VA05062470	0.80
							s/q	3																					
6	1	2.0	7.0	50		3.0	q/chl	3			5.0		9.0					1.0	3.0			B382365	245.36	246.69	1.770			VA05062470	1.33
							cb	3																					
6	6	0.1	0.6	35		1.0	q/cb	3		100.0								4.0											
5	1	1.3	3.5	35		5.0	q/chl	3		5.0		5.0										B382366	246.69	248.41	0.042			VA05062470	1.72
4	1	3.0	6.0	10	60	2.0	q/cb	3			9.0		10.0									B382367	248.41	249.94	0.419			VA05062470	1.53
5	1	1.3	5.0			1.0	q/chl	2			3.0											B382368	249.94	251.46	0.027		random orientations of veins - all rearranged	VA05062470	1.52
5	1	1.3	5.0			1.0	q/chl	2			3.0											B382369	249.94	251.46	0.028	PD/CA		VA05062470	1.52
																						B382370	STANDARD 7G		4.420	7G		VA05062470	
7	4	0.2	1.4	15																		B382371	251.46	252.98	0.029			VA05062470	1.52
5	1	1.0	5.0	70	50	0.5	q/chl	2	1	40.0	40.0							3.0											
2	1	3.0	4.5	50		1.0	q	2	0		5.0		4.0					1.0	3.0			B382372	252.98	254.51	0.033			VA05062470	1.53
2	6	0.2	0.4	100		1.0	q/cb	3	0	40.0	20.0							4.0											
							chl	1																					
4	1	1.5	4.5	50		2.0	q/chl	3	0		20.0							1.0				B382373	254.51	256.03	0.026			VA05062470	1.52
							cb	1																					
5	1	2.0	8.0	50		1.0	q/chl	3	0	3.0	5.0		20.0					3.0				B382374	256.03	257.56	0.626			VA05062470	1.53
							cb	1																					
4	1	1.2	4.0	50		1.0	q/chl	2	0													B382375	257.56	259.08	0.027			VA05062470	1.52
							cb	2																					
																						B382376	BLANK		<0.005			VA05062470	
3	6	0.5	1.2	40	120	0.0				100.0								2.0				B382377	259.08	259.90	0.034			VA05062470	0.82
6	6	0.3	2.0	40	90	2.0	b/q	1	0	100.0								4.0				B382378	259.90	260.60	0.062			VA05062470	0.70
1	1	1.5	1.5	40		1.0	q/chl	3	0																				
3	1	1.5	4.0	45	80	2.0	q/cb	3	1				0.1									B382379	260.60	262.13	0.027		qtz veins all rearranged	VA05062470	1.53
							chl	1																					
5	6	0.5	1.8	20	35	5.0	cb	5	2	100.0								4.0											
4	1	1.5	5.5	65	45	0.0							0.1									B382380	262.13	263.04	0.062		bunched' sulph. Veins into 15cm lengths w/in GND texture	VA05062470	0.91
40	6	0.2	35.0	45						90.0	10.0			0.1	0.1			4.0											
3	1	1.0	3.0	120		1.0	q/cb	3	1		5.0		5.0					2.0	4.0			B382381	263.04	263.65	0.018			VA05062470	0.61
							cb	3																					
20	6	0.5	3.0	50			cb	3		100.0								4.0											
3	1	1.0	3.0	120		1.0	q/cb	3	1		5.0		5.0					2.0	4.0			B382382	263.04	263.65	0.036	DUP		VA05062470	0.61
20	6	0.5	3.0	50			cb	3		100.0								4.0											
2	1	1.0	2.0	50		1.0	q	2			5.0		5.0					2.0	4.0			B382383	263.65	264.38	0.061			VA05062470	0.73
4	6	0.2	0.8	50						100.0								4.0											
2	4	0.5	1.0	65		2.0	cb	4		5.0			5.0					5.0	4.0			B382384	264.38	265.18	0.034			VA05062470	0.80
4	1	1.0	3.5	115		2.0	q/cb	3																					
3	4	0.2	0.6	30		0.5	cb	2		5.0								5.0				B382385	265.18	265.99	0.007			VA05062470	0.81
1	1	0.6	0.6	130		1.0	q	3					15.0						4.0										
3	4	0.2	0.6	20	35	1.0	cb	3		5.0								5.0				B382386	265.99	266.57	0.009			VA05062470	0.58
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-292C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 750m

BEARING: 000 | DIP: -50°

DATE STARTED: 08-Jul-05 | DATE COMPLETED: 10-Jul-05

LOGGED BY: Terry Croteau Jul.8-12, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 458490 NORTHING: 70985567

COORD SYSTEM: NAD 83: EASTING: 458371 NORTHING: 7098567

NAD 27 (CORRECTED for historic grid): EASTING: 458460 NORTHING: 7098577

SECTION LINE(historic grid): 458460

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 1.53m

Deviation:

Casing: 12.19m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B380611 to B380791 (all)

Requisition #: MASP448STRGOL.05Q Date Shipped: 15-Jul-05

Lab Record #: VA05060561 Date Received: 22-Jul-05

Duplicates:	B380622, B380642, B380662, B380682, B380702, B380722, B380742, B380762, B380782,
Preparation Duplicate/ Check Assay:	B380629, B380649, B380669, B380689, B380709, B380729, B380749, B380769, B380789,
Standards:	B380630(3C), B380650(4D), B380670(5E), B380690(2B), B380710(5E), B380730(3C), B380749(1A), B380770(4D), B380790(3C)
Blanks:	B380616, B380636, B380656, B380676, B380696, B380716, B380736, B380756, B380776,

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
202.7	346.6	51.9	012.6	013.6
18.3	340.0	47.3	006.0	007.0
100.6	344.3	49.0	010.3	011.3

LITHOLOGY

FROM	TO	
12.19	202.69	MSED

ALTERATION

FROM	TO	

MINERALIZATION (Veins)

FROM	TO	

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1 | **DATE: July 8 = 10th, 2005** | **PAGE 1 of 8**

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-12.19			CASING						
1	12.19-13.72			OVB: Core is broken, 70% rounded pebbles of qtz, QZZ, MSED, + other detrital material. Likely from drilling on washed gravel pile. Poor recovery.						
70	13.72-25.91			QZZ: 90% qtz, 5% k-feld, 3% bt, ±2% sulphides						
70		13.72	15.24	Core is broken. Silicous, lim staining on fract faces. Some fracture faces have clay on surface. Fractures are filled w/ sulphides py, aspy. Diss py and aspy can also be found. At 14.94m, a- 30cm qtz vein. Unable to determine angle or contact. Light grey colour, fractures ox'd, tr py.	1			1		
70		15.24	19.81	Core becomes more broken, still highly silicious. Less lim on frac faces. Veinlets of sulphides, also fracture fill, and small (<1mm) euhedral py crystals on frac faces.	1					
70		19.81	21.34	Fracture are heavily stained by lim. Minor ser can be found on a few (5%) of frac faces. Py and aspy fill irregular fractures. Also found as diss sulphides	2	1				
70		21.34	25.91	Core is broken into mostly (80%) gravel to cobble size pieces. Minor lim staining on pebbles from 22.86 to 23.10m. Minor clay on frac surfaces. Diss py found throughout.	1			1		
70		25.91	27.43	Core is dark grey, still. Silicious, minor lim staining, no clay.						
80	27.43-38.10	27.43	28.13	MSED. Core is dark grey to black, fine gr. Qtz eyes and lenses are present. Black colour is due to graphite. Foliation present, but no preferred orientation, instead "s". Possible fault (looks similar to 287C). Diss py on faces (1%).						
80		28.13	28.96	Core is light grey, with white laminae. Silicious with ser on faces. Foliations at 40° to CA. At 28.73m, 23cm clay gouge contains MSED frags.		2		3		
80		28.96	33.53	Bleached, silicified MSED. Core is a light tan colour. Foliation often difficult to distinguish, overprinted. Where visible it ranges from 65-75°. Chl common on fractures, as is ser and clay.		2	2	2		
80		33.53	38.10	Core is less silicious. Chl alt'n more intense, ser and clay alt'n is reduced. Foliation at 45-50°.		1	3	1		
81	38.10	38.10	48.77	HFLS: Core is foliated. Colour is banded brown, violet and green. Foliation is at 50° to CA until 42.87m, where it is at 70°to CA. It returns to 50-60° at 49.20m. Very few qtz veins or sulphides are present. Fractures are filled with chl, ser, and minor carb. Frac faces show the same. The qtz veins that do exist run parallel to foliation. At 43.04m, 2cm clay gouge. Core on either side shows slickensides. Core is soft, easy to scratch - chl.		2	2	1	1	
80	48.77-49.37	48.77	49.37	HFLS giving way to more silicious MSED. Foliations no longer visible. Increase in carb veinlets. Trace py on fractures.		1	1		2	
81	49.37-56.39	49.37	56.39	HFLS - Similar to HFLS at 38.10m, with more intense clay and chl alteration. Frequent areas of gouge. Foliation at 50-55° from 49.37 to 53.43m, at 60-65° from 53.43 to 56.39m. At 51.52m, 3cm gouge at 45° to CA. At 53.04m, 6cm clay gouge at 70° to CA. At 54.52m, 4cm gouge at 70° to CA.		1	3	3	1	
80	56.39-59.44	56.39	59.44	MSED - Silicified, difficult to scratch. No visible foliation. Minor ser on frac.		1		1	1	
81	59.44-62.48	59.44	61.56	HFLS. Foliation at 80°, minor clay alt'n.		1	2	1	1	
81		61.56	62.48	HFLS heavily alt'd to clay (80%). Small fragments of HFLS found within		1	2	4	1	
80	62.48-64.71	62.48	64.71	MSED - Silicious MSEDs. Foliation is difficult to distinguish: From 62.48-64.01m, @80° to CA; From 64.01-64.71m, @50° to CA. At 62.75m, 10cm trace py on frac faces w/ slickensides.		1	1	1		
81	64.71-65.53	64.71	65.53	HFLS. Chl and clay on fracs. Foliation at 80°, crenulations		2	2	1	1	
80	65.53-67.06	65.53	67.06	Silicious MSED. Black, with white, 1mm bands at 85° to CA. Contact with hornfels at 70°		1	1	1		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B380611	12.19	13.72	0.006			VA05060561	1.53
2	1	30.0								1.0												B380612	13.72	15.24	0.041		no vein contacts. veins are broken, or in pieces.	VA05060561	1.52
	4																					B380613	15.24	16.76	0.137			VA05060561	1.52
2	6	0.1	0.2	65									1.0					10.0				B380614	16.76	18.29	0.025			VA05060561	1.53
3	6	0.1	0.3	65						1.0								10.0				B380615	18.29	19.81	0.113			VA05060561	1.52
																						B380616	BLANK		<0.005			VA05060561	
3	6	0.1	0.3	65						1.0			1.0									B380617	19.81	22.86	0.025		B380617 is 3m sample; Tag B380618 was misplaced.	VA05060561	3.05
2	1	0.5	0.7	50						1.0			1.0									B380619	22.86	24.38	0.011			VA05060561	1.52
4	1	0.2	0.8	50						0.1												B380620	24.38	25.91	0.084			VA05060561	1.53
2	6	0.2	0.4	50						1.0			1.0									B380621	25.91	27.43	0.012			VA05060561	1.52
2	6	0.2	0.4	50						1.0			1.0									B380622	25.91	27.43	0.012	DUP		VA05060561	1.52
0																						B380623	27.43	28.13	0.009			VA05060561	0.70
0																						B380624	28.13	28.96	<0.005			VA05060561	0.83
2	3			15																		B380625	28.96	30.48	<0.005		veinlets	VA05060561	1.52
7	3			15																		B380626	30.48	32.00	<0.005		veinlets	VA05060561	1.52
0																						B380627	32.00	33.53	<0.005			VA05060561	1.53
																						B380628	33.53	35.05	<0.005			VA05060561	1.52
																						B380629	33.53	35.05	<0.005	PD/CA		VA05060561	1.52
																						B380630	STANDARD 3C		0.088	3C		VA05060561	
2	1	0.2	0.4	40	175								0.1									B380631	35.05	36.58	0.007			VA05060561	1.53
5	1	1.0	1.6	50						2.0												B380632	36.58	38.10	<0.005			VA05060561	1.52
	4																					B380633	38.10	39.62	<0.005		veinlets at same orientation as foliation	VA05060561	1.52
1	1	7.0	7.0	55		2	chl	4	0	0.1												B380634	39.62	41.15	0.005			VA05060561	1.53
	4																					B380635	41.15	42.67	<0.005		veinlets at same orientation as foliation	VA05060561	1.52
																						B380636	BLANK		<0.005			VA05060561	
1	1	1.0	1.0	50						1.0												B380637	42.67	44.20	<0.005		vein between foliation	VA05060561	1.53
1	4	0.2	0.2	35																		B380638	44.20	45.72	<0.005			VA05060561	1.52
	4			35																		B380639	45.72	47.24	<0.005		carb veinlets	VA05060561	1.52
2	1	0.2	0.4	50							0.1											B380640	47.24	48.77	<0.005			VA05060561	1.53
3	1	1.0	1.4	85	145						0.0											B380641	48.77	49.37	0.008		veins at 145°crosscut foliation	VA05060561	0.60
3	1	1.0	1.4	85	145						0.0											B380642	48.77	49.37	0.006	DUP		VA05060561	0.60
	4			40	50																	B380643	49.37	50.29	<0.005		carb veinlets	VA05060561	0.92
	4			45	55																	B380644	50.29	51.82	0.005		carb veinlets	VA05060561	1.53
1	1																					B380645	51.82	53.34	<0.005		irregular fracture fill	VA05060561	1.52
1	1	3.0	3.0	85						1.0												B380646	53.34	54.86	<0.005		py in tension gashes	VA05060561	1.52
0																						B380647	54.86	56.39	<0.005			VA05060561	1.53
	4			5	10																	B380648	56.39	57.91	0.007			VA05060561	1.52
	4			5	10																	B380649	56.39	57.91	<0.005	PD/CA		VA05060561	1.52
																						B380650	STANDARD 4D		0.431	4D		VA05060561	
	4			80																		B380651	57.91	59.44	<0.005		carb veinlets	VA05060561	1.53
				80																		B380652	59.44	60.91	<0.005		carb veinlets	VA05060561	1.47
																						B380653	60.91	61.56	<0.005			VA05060561	0.65
0																						B380654	61.56	62.48	<0.005			VA05060561	0.92
	4			30	130																	B380655	62.48	64.01	<0.005		carb veinlets	VA05060561	1.53
																						B380656	BLANK		<0.005			VA05060561	
	4			30																		B380657	64.01	64.71	<0.005		carb veinlets	VA05060561	0.70
	4			80																		B380658	64.71	65.53	<0.005		carb veinlets	VA05060561	0.82
	4			45	80																	B380659	65.53	67.06	0.010			VA05060561	1.53

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81	67.06-70.98	67.06	70.98	HFLS. Foliation at 85-90° to CA. Qtz intrudes between foliations at 69.72m and contain 1% py. Chl and ser on frac faces.		2	2	1	1	
80	70.98-73.15	70.98	73.15	Silicious MSED. No visible foliation. Increase in veining, with minor sulphides. Core is black with green bands. Frac faces @72.70m show py on them. Contact w/ hornfels at 70°						
81	73.15-81.80	73.15	74.68	Foliation at 80° to CA. At 73.40m, 6cm grey qtz vein, at 80° to CA, trace py. At 73.97m, silicified MSED, ser on frac's.		2	2	1		
81		74.68	76.20	Very poor recovery (16%), pieces of qtz vein (3-5cm) and HFLS. At 76.18m, 2cm gouge, sandy.						
81		76.20	81.80	HFLS. Foliation at 60°. Qtz intrudes foliation or crosscuts. Chl content increases after 79.25m. At 79.25m, foliation becomes 70-75°. At 81.32m, foliation at 80-85°.		2	3	1	1	
80	81.80-82.30	81.80	82.30	Silicious MSED. Fractures filled w/ carb light grey colour. Py on frac surface (tr.). At 82.10m, 3cm sandy gouge at 40°. Contact w/ HFLS to 80°.				1	2	
81	82.30-83.72	82.30	83.72	HFLS. Foliation @ 75-80°. Slightly more clay alt'n. At 82.73m, 5cm grey qtz vein @90° to CA.						
80	83.72-85.15	83.72	85.15	Silicious MSED w/ interbedded HFLS. Foliation only visible in the HFLS at 80-85° to CA. Tr py on MSED frac faces.		1	2	1		
81	85.15-87.43	85.15	86.56	HFLS. Foliation @ 80-85° to CA. Core has a slight green tinge to it - chl dominant alt'n. Minor ser and clay on frac. Smells like sulphur when scratched - minor sphalerite		1	3	2		
		86.56	86.87	~20cm grey qtz vein, broken, no visible contacts. 15-20% massive sulphides: py + aspy						
		86.87	87.43	Broken pieces of qtz vein w/ py and aspy as massive sulphides. Also pieces of silicified MSED.						
80	87.43-91.44	87.43	91.44	MSED. Silicified, no visible foliation or contact. Tan coloured clay on frac surfaces.				1		
81	91.44-92.96	91.44	92.96	HFLS. Foliation @ 75-80°. Qtz veins intrude foliation. Carb veinlets follow foliation at 75-80°		1	3	2		
80	92.96-94.86	92.96	94.86	Silicified MSED. Foliation difficult to see, but @ 45-50° where visible. At 93.16m, 7cm grey qtz vein. Bismuthinite on frac face.						
81	94.86-101.88	94.86	101.88	HFLS. Foliation at 94.86m at 70°, at 96.01m, 75-80°, at 97.56m, 55-60°, at 99.06m, 55-60°, at 100.56m, 60-65°. Clay and chl alt'n common. Cb veinlets abundant.		1	3	2	1	
80	101.88-105.16	101.88	105.16	MSED. Silicified, foliation @ 101.81m - 85-90°, @102.11m - 70-75°, @103.63m - 75-80°. Foliation is difficult to distinguish due to overprinting. At 104.08m, 8cm tan coloured sandy gouge. MSED frags present.		1	2	2		
81	105.16-111.25	105.16	107.20	Silicified HFLS. Does not scratch easily. Less chl and ser alt'n. Violet and green colour. Foliation at 60°.		1	1	1		
81		107.20	111.25	HFLS. Easy to scratch, higher chl content - more green banding. Foliation @ 107.2m - 80°, @108.20m, 90-95° - crenulated for 9cm. After this, @110°. @109.73m - 110°. @110.33, 4cm clay gouge @80° to CA. @110.82m, 5cm clay gouge @70° to CA.		2	2	2	1	
80	111.25-114.30	111.25	114.30	Silicified MSEDS. Foliation visible: @111.25m, 60-65°. @112.78m, 70-75°. @111.99m, 10 cm qtz vein grey qtz @80° to CA. Contains 1% po. Diss py present, also intrudes foliation.		1	1	1		
81	114.30-115.54	114.30	115.54	HFLS. Easily scratched by nail. Foliation @60-65° to CA. Chl on frac faces. Carb veins return, crosscut foliation		1	3	2	1	
80	115.54-116.50	115.54	116.50	Silicious MSED. Light grey color. Carb on frac faces. Foliations @ 75-80° to CA					1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2006

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
	1																					B380660	67.06	68.58	<0.005		qtz intrudes foliation	VA05060561	1.52
2	1	1.0	1.2	60						1.0												B380661	68.58	70.10	<0.005			VA05060561	1.52
2	1	1.0	1.2	60						1.0									.			B380662	68.58	70.10	<0.005	DUP		VA05060561	1.52
1	1	1.0	1.0	70																		B380663	70.10	70.98	<0.005		no visible sulphides	VA05060561	0.88
5	4	0.1	0.5	35																		B380664	70.98	71.63	<0.005			VA05060561	0.65
																						B380665	71.63	73.15	<0.005			VA05060561	1.52
1	1	5.0	5.0	50						0.1												B380666	73.15	74.68	<0.005			VA05060561	1.53
1	1	5.0								0.1												B380667	74.68	76.20	0.015		broken into pieces, may be larger than 5cm	VA05060561	1.52
3	1	2.0	6.0	60						0.1												B380668	76.20	77.22	<0.005			VA05060561	1.02
3	1	2.0	6.0	60						0.1												B380669	76.20	77.22	<0.005	PD/CA		VA05060561	1.02
																						B380670	STANDARD 5E		1.505	5E		VA05060561	
2	1	0.5	1.0																			B380671	77.72	79.25	<0.005		veins irregular	VA05060561	1.53
2	1	0.5	1.0																			B380672	79.25	80.77	<0.005		veins irregular	VA05060561	1.52
0																						B380673	80.77	81.80	<0.005			VA05060561	1.03
7	4	0.2	1.4	20																		B380674	81.80	82.30	<0.005		carb veinlets	VA05060561	0.50
1	1	5.0	5.0	90							1.0											B380675	82.30	83.72	<0.005			VA05060561	1.42
																						B380676	BLANK		<0.005			VA05060561	
4	1	2.0	3.0	85							0.1											B380677	83.72	85.15	<0.005		veins irregular; only 1 at 85°	VA05060561	1.43
2	1	0.2	0.4																			B380678	85.15	86.56	<0.005		irregular, intrude between foliations	VA05060561	1.41
1	1	20.0	20.0							20.0			15.0									B380679	86.56	86.87	0.280			VA05060561	0.31
1	1									10.0			10.0									B380680	86.87	87.43	0.014		broken into gravel size pieces	VA05060561	0.56
2	1	1.5	1.7	80		8	5	4		1.0												B380681	87.43	88.39	<0.005			VA05060561	0.96
2	1	1.5	1.7	80		8	5	4		1.0												B380682	87.43	88.39	<0.005	DUP		VA05060561	0.96
	4			25																		B380683	88.39	89.92	0.005		cb veinlets	VA05060561	1.53
	4			30																		B380684	89.92	91.44	<0.005		cb veinlets	VA05060561	1.52
	4			60	20																	B380685	91.44	92.96	<0.005		cb veinlets	VA05060561	1.52
1	1	7.0	7.0			15	q	4	0	0.1												B380686	92.96	94.49	<0.005		bismuthinite on frac face	VA05060561	1.53
1	1	0.5	0.5	80																		B380687	94.49	94.86	<0.005			VA05060561	0.37
	4			60																		B380688	94.86	96.01	<0.005		cb veinlets	VA05060561	1.15
	4			60																		B380689	94.86	96.01	<0.005	PD/CA		VA05060561	1.15
																						B380690	STANDARD 2B		3.290	2B		VA05060561	
	4			50																		B380691	96.01	97.56	<0.005		cb veinlets	VA05060561	1.55
0																						B380692	97.56	99.06	0.012			VA05060561	1.50
0																						B380693	99.06	100.58	<0.005			VA05060561	1.52
0																						B380694	100.58	101.88	<0.005			VA05060561	1.30
2	1	0.5	1.0																			B380695	101.88	102.11	<0.005		pieces, unable to attain orientation	VA05060561	0.23
																						B380696	BLANK		<0.005			VA05060561	
1	1	1.0	1.0	85																		B380697	102.11	103.63	0.008			VA05060561	1.52
	2			60																		B380698	103.63	105.16	<0.005		veinlets	VA05060561	1.53
	2			60																		B380699	105.16	106.68	<0.005		veinlets	VA05060561	1.52
1	1	5.0	5.0	40						1.0												B380700	106.68	107.20	0.010		irregular shape	VA05060561	0.52
	2			65																		B380701	107.20	108.20	<0.005		veinlets	VA05060561	1.00
																						B380702	107.20	108.20	<0.005	DUP		VA05060561	1.00
1	1	2.0	2.0	70		2	chl	5	0	0.1												B380703	108.20	109.73	<0.005			VA05060561	1.53
	2	25.0																				B380704	109.73	111.25	0.005		veinlets	VA05060561	1.52
1	1	1.0	1.0	90																		B380705	111.25	111.99	<0.005			VA05060561	0.74
1	1	10.0	10.0	85		3	chl	4	0		1.0											B380706	111.99	112.17	<0.005			VA05060561	0.18
	2			25																		B380707	112.17	112.78	<0.005		veinlets	VA05060561	0.61
	2			30	175																	B380708	112.78	114.30	<0.005		veinlets	VA05060561	1.52
																						B380709	112.78	114.30	<0.005	PD/CA		VA05060561	1.52
																						B380710	STANDARD 5E		1.475	5E		VA05060561	
2	4	0.1	0.2	50																		B380711	114.30	115.54	<0.005			VA05060561	1.24
	2			80																							veinlets		
	2			170																		B380712	115.54	116.50	0.021		veinlets	VA05060561	0.96

DRILL LOG LEGEND P1	DATE: July 8 = 10th, 2006	PAGE 5 of 8		
DRILL HOLE # : DG05-292C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81	116.50-117.35	116.50	117.35	HFLS. Soft, easily scratchable. Foliation @ 70-75° to CA. Chl alt'n dominant.		1	2	2	1	
80	117.35-118.87	117.35	118.87	Silicious MSED. Dark grey, banded. Foliation @ 70-75°.						
81	118.87-123.44	118.87	123.44	HFLS and silicious MSED, interbedded. Foliation @119.07m - 45-50°, @120.90m - 70-75°; @ 121.92m - 60-65°. The HFLS has lower angle foliation than the MSED.		1	2	1	1	
80	123.44-202.69	123.44	125.83	MSED. Chloritized with several large (> 5cm) qtz veins. Carb on frac faces and in veinlets. Some veins are irregular, some follow foliation. @123.49m, 8cm grey qtz vein @ 65° to CA @124.47m, 8cm grey qtz vein @ 75° to CA, tr py @124.73m, 10cm qtz vein @40° to CA, 1% po			3		2	
80		125.83	134.11	Foliation @ 125.83m - 55-60°, @126.49m - 55-60°, @128.02m - 55-60°, @129.59m - 70-75°, @131.06m - 75-80°, @132.59m - 85-90° to CA. Cb veinlets crosscut foliation as do sulphides, which are rare containing only trace amounts.		1	2	1	1	
80		134.11	147.83	MSED Silicious, dark brown to dark grey. Most qtz veins run between foliations. Some are irregular shape, as well as filled gashes. Foliation @134.11m - 85-90°, @135.64m - 85-90°, @137.16m - 85-90° - aspy crystals on frac faces @138.68m - 85-90° @140.24m - 75-80° @141.73m - 65-70° @143.26m - 70-75° - diss po and cpy @144.78m - 70-75° - diss po and cpy @146.30m - 65-70° - diss po and cpy There is an increase in shear over this interval. Boudins are present starting at 144.78m and continuing until 154.85m.		2			1	
80		147.83	149.35	Core is light green, contains abundant ser, chl. Trace diss po present.		2	2	1		
80		149.35	154.85	MSED Grey green to grey. Shear is highly visible as boudins. Foliation @149.35m - 55-60° @150.88m - 45-50° @152.40m - 65-70° @153.92m - 65-70° Qtz fills gashes, crosscutting foliation or follows foliation or crenulation. Diss py occurs from 149.35 - 152.40m in darker core. Diss aspy occurs from 152.40-154.85m in lighter coloured core		2	2	1	1	
80		154.85	158.50	Core is light green to white. Ser alt'n. Veining increases, filling gashes and between foliation. Carb alt'n increases. Foliation @ 65 - 70° to CA. Shearing indicators absent.		3	1		2	
80		158.50	161.54	Silicified MSEDS. Foliation is difficult to distinguish, most has been overprinted. Dissem aspy, vnlets and euhedral crystals on frac face. Foliation (where visible) @ 50-55°.						
80		161.54	175.26	MSED and HFLS interbedded. Boudins present--increased shear. Carb alt'n increased. Foliations at: 161.54m--60-65°; 163.07m--65-70° (7cm qtz vn @163.82m); 164.59m--65-70° (8cm qtz vn @ 165.21m); 166.12m--60-65°; 167.64m--65-70°; 169.16m--60-65°; 170.69m--75-80°; 172.21m--55-60°; 173.74m--60-65°. Qtz vns follow foliation. Trace dissem py present. Sulphide content increased compared to other intervals.		2	2	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	75																		B380713	116.50	117.35	0.007			VA05060561	0.85
	4			170																		B380714	117.35	118.87	<0.005		veinlets	VA05060561	1.52
2	3	0.2	0.4	50	162																	B380715	118.87	120.40	<0.005			VA05060561	1.53
																						B380716	BLANK		<0.005			VA05060561	
2	4	0.2	0.4	55																		B380717	120.40	121.92	<0.005		veinlets	VA05060561	
2	1	4.0	6.0	45	65					0.1												B380718	121.92	123.44	<0.005			VA05060561	1.52
3	1	11.0	26.0	40	75					0.1	1.0											B380719	123.44	124.97	<0.005			VA05060561	1.53
3				170																		B380720	124.97	125.83	<0.005		veinlets	VA05060561	0.86
3	1	0.2	0.6	70							0.1											B380721	125.83	126.49	<0.005			VA05060561	0.66
3	1	0.2	0.6	70							0.1											B380722	125.83	126.49	<0.005	DUP		VA05060561	0.66
3	1	0.2	0.6	80							0.1											B380723	126.49	128.02	<0.005			VA05060561	1.53
2	1	1.0	1.5	60																		B380724	128.02	129.59	<0.005			VA05060561	1.57
	4			50																		B380725	129.59	131.06	<0.005		veinlets	VA05060561	1.47
	4			55																		B380726	131.06	132.59	<0.005		veinlets	VA05060561	1.53
	4			50																		B380727	132.59	134.11	<0.005		veinlets	VA05060561	1.52
2	1	2.0	3.0	80																		B380728	134.11	135.64	<0.005			VA05060561	1.53
2	1	2.0	3.0	80																		B380729	134.11	135.64	0.005	PD/CA		VA05060561	1.53
																						B380730	STANDARD 3C		0.092	3C		VA05060561	
	2			30																		B380731	135.64	137.16	<0.005		veinlets	VA05060561	1.52
	1																					B380732	137.16	138.68	<0.005		irregular fill/gashes	VA05060561	1.52
1	1	1.0	1.0	50																		B380733	138.68	140.24	<0.005			VA05060561	1.56
1	6	0.1	0.1	160						0.1								95.0				B380734	140.24	141.73	0.007			VA05060561	1.49
1	1	1.0	1.0	50							1.0											B380735	141.73	143.26	<0.005			VA05060561	1.53
																						B380736	BLANK		<0.005			VA05060561	
2	3	0.5	1.0	30																		B380737	143.26	144.78	0.517		Diss po and cpy	VA05060561	
1	1	0.5	0.5	70																		B380738	144.78	146.30	<0.005		Diss po and cpy	VA05060561	1.52
3	6	0.1	0.3	160						0.1								95.0				B380739	146.30	147.83	<0.005			VA05060561	1.53
1	3	0.5	0.5	10																		B380740	147.83	149.35	<0.005			VA05060561	1.52
1	1	5.0	5.0	55						0.1												B380741	149.35	150.88	0.005			VA05060561	1.53
1	1	5.0	5.0	55						0.1												B380742	149.35	150.88	0.007	DUP		VA05060561	1.53
2	3	0.1	0.2	30																		B380743	150.88	152.40	0.008			VA05060561	1.52
1	1	2.0	2.0	60						1.0												B380744	152.40	153.92	<0.005			VA05060561	1.52
5	1	2.0	3.0	60																		B380745	153.92	154.85	<0.005			VA05060561	0.93
	1	0.5																				B380746	154.85	155.40	<0.005		filled gashes	VA05060561	0.55
5	1	3.0	6.0	70																		B380747	155.40	156.97	<0.005			VA05060561	1.57
0																						B380748	156.97	158.50	0.010			VA05060561	1.53
																						B380749	156.97	158.50	0.009	PD/CA		VA05060561	1.53
																						B380750	STANDARD 1A		0.871	1A		VA05060561	
6	6	0.1	0.6	30						1.0								70.0				B380751	158.50	160.02	<0.005			VA05060561	1.52
2	3	0.2	0.4	25																		B380752	160.02	161.54	0.011			VA05060561	1.52
3	3	0.2	0.6	27																		B380753	161.54	163.07	<0.005			VA05060561	1.53
5	1	7.0	15.0	80						1.0			2.0									B380754	163.07	164.59	0.005			VA05060561	1.52
2	1	8.0	9.0	85						0.1												B380755	164.59	166.12	<0.005			VA05060561	1.53
																						B380756	BLANK		<0.005			VA05060561	

DRILL LOG LEGEND P1

DATE: July 8 = 10th, 2005 PAGE 7 of 8

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		175.26	181.36	Silicified MSED. Light grey green color. Foliation is difficult to see, when foliation is visible boudins present. Foliations at: 175.26m--55-60°; 176.68m--55-60°; 178.31m--45-50°; 179.83m--45-50°. Dissem aspy present @ 176.78m-178.31m. At 178.56m: 15cm sandy texture-ss. Increase in carb vning.		1	1		1	
80		181.36	182.88	Dark grey MSED. Boudins still present-shear. Frac faces show chl. Foliation @ 65-70° to CA.		2	2	1	1	
80		182.88	185.03	MSED are light grey and silicified, boudins are reduced, possibly overprinted. Foliation is difficult to see. Foliation @: 182.88m--80-85°; 184.40m--85-90°. Vns btwn foliations.						
80		185.03	185.60	MSED dark grey, boudins again visible. Foliation @ 80-85°. Qtz vns btwn foliations.		2	2		1	
80		185.60	185.85	25cm white qtz vn @ 60° to CA. Trace py and aspy.						
80		185.85	186.65	Silicified MSED. Carb on frac faces, boudins present-shear. Foliation overprinted, but where visible @ 85° to CA. Qtz vns crosscut foliation, and run parallel. Light grey color, large number of qtz vns (10).			1		2	
80		186.65	188.98	Dark grey MSED. Soft, easily scratched. Boudins present w/ dissem aspy. Qtz vns less common. Foliation @ 85-90°.		2	2		1	
80		188.98	193.55	Dark grey MSED. Harder to scratch, silicious. Very little foliation is visible @ 75-80°. Trace cb on frac faces, boudins visible where foliation visible.			1		1	
80		193.55	194.47	Easily scratchable, green to grey color. Chl on frac faces, foliation @ 65° to CA.		2	2		1	
80		194.47	195.07	Core is light grey green, silicious. No visible foliation.						
80		195.07	202.69	MSED, soft, easily scratchable. Colour varies from green to grey. Boudins visible throughout section. Foliation @: 195.07m--75-80°; 196.60m--55-60° (dissem aspy); 198.12m--55-60°; 199.69m--85-90°; 201.17m--65-70°. Vns follow foliation, most have irregular shape.						
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
2	1	1.0	1.5	60																		B380757	166.12	167.64	<0.005			VA05060561	1.52
5	6	0.1	0.5	5	10								2.0									B380758	167.64	169.16	<0.005			VA05060561	1.52
3	1	0.5	0.9	65																		B380759	169.16	170.69	0.008			VA05060561	1.53
3	1	1.0	1.4	60									0.1									B380760	170.69	172.21	<0.005			VA05060561	1.52
2	3	0.5	1.0	7																									
2	3	0.5	1.0	10																		B380761	172.21	173.74	<0.005			VA05060561	1.53
2	3	0.5	1.0	10																		B380762	172.21	173.74	<0.005	DUP		VA05060561	1.53
	3			10																		B380763	173.74	175.26	<0.005		vnlets	VA05060561	1.52
1	1	6.0	6.0	70						1.0												B380764	175.26	176.78	<0.005			VA05060561	1.52
4	1	1.5	3.0	40	70					1.0			0.1									B380765	176.78	178.31	0.017			VA05060561	1.53
3	1	1.5	3.0	45						0.1												B380766	178.31	179.83	0.005			VA05060561	1.52
1	6	0.2	0.2	35						3.0								10.0											
1	1	2.0	2.0	65						0.1												B380767	179.83	181.36	0.005			VA05060561	1.53
1	1	2.0	2.0	70																		B380768	181.36	182.88	0.022			VA05060561	1.52
1	1	2.0	2.0	70																		B380769	181.36	182.88	0.023	PD/CA		VA05060561	1.52
																						B380770	STANDARD 4D		0.429	4D		VA05060561	
4	1	9.0	12.0	65						1.0												B380771	182.88	184.40	0.011			VA05060561	1.52
5	1	3.0	11.0	65						1.0												B380772	184.40	185.03	<0.005			VA05060561	0.63
4	1	4.5	9.0	65						0.1												B380773	185.03	185.60	<0.005			VA05060561	0.57
1	1	25.0	25.0	60						0.1			0.1									B380774	185.60	185.85	<0.005			VA05060561	0.25
11	1	5.0	15.0	60						0.1			0.1									B380775	185.85	186.65	<0.005			VA05060561	0.80
																						B380776	BLANK		<0.005			VA05060561	
1	1	3.0	3.0	75																		B380777	186.65	187.45	<0.005			VA05060561	0.80
2	1	3.0	3.0	85						0.1												B380778	187.45	188.98	0.006			VA05060561	1.53
3	1	1.0	3.0	85	80								0.1									B380779	188.98	190.50	0.005			VA05060561	1.52
8	1	2.0	6.0	80						0.1												B380780	190.50	192.02	0.005			VA05060561	1.52
2	2	0.2	0.4	75						0.1			0.1									B380781	192.02	193.55	0.035			VA05060561	1.53
2	2	0.2	0.4	75						0.1			0.1									B380782	192.02	193.55	0.025	DUP		VA05060561	1.53
4	1	2.0	5.0	75									0.1									B380783	193.55	194.47	<0.005			VA05060561	0.92
3	6	0.1	0.3	15						1.0																			
2	1	0.2	0.4	75									0.1									B380784	194.47	195.07	0.008			VA05060561	0.60
3	1	1.0	1.4	80									0.1									B380785	195.07	196.60	<0.005			VA05060561	1.53
1	6	0.2	0.2	50						3.0												B380786	196.60	198.12	<0.005			VA05060561	1.52
3	1	1.0	2.0	55									0.1						95.0			B380787	198.12	199.69	<0.005			VA05060561	1.57
1	3	0.2	0.2	30																		B380788	199.69	201.17	<0.005			VA05060561	1.48
1	3	0.2	0.2	30																		B380789	199.69	201.17	0.005	PD/CA		VA05060561	1.48
																						B380790	STANDARD 3C		0.092	3C		VA05060561	
4	1	1.0	2.5	75							0.1											B380791	201.17	202.69	<0.005			VA05060561	1.52
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-293C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 762m

BEARING: 000 | DIP: -50°

DATE STARTED: 11-Jul-05 | DATE COMPLETED: 14-Jul-05

LOGGED BY: Terry Croteau July 13-16, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 458456 NORTHING: 7098452

COORD SYSTEM: NAD 83: EASTING: 458337 NORTHING: 7098635

NAD 27 (CORRECTED for historic grid): EASTING: 458426 NORTHING: 7098462

SECTION LINE(historic grid): 458426E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 15.24m

Deviation:

Casing: 18.29m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
15.24	19.81	OVB
19.81	21.34	QZZ
21.34	22.86	OVB
22.86	36.58	QZZ
36.58	59.44	MSED
59.44	60.96	OVB (contamination?)
60.96	102.28	MSED
102.28	103.63	DIOR (mafic intrusive)
103.63	166.12	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B380792-B380836

Requisition #: MASP448STRGOL.05Q Date Shipped: 15-Jul-05

Lab Record #: VA05060560 Date Received: 22-Jul-05

Sample Sequence: B380837-B380922

Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05

Lab Record #: VA05062472 Date Received: 27-Jul-05

Duplicates:	B380802; B380822; B380842; B380862; B380882; B380902; B380922
Preparation Duplicate/ Check Assay:	B380809; B380829; B380849; B380869; B380889; B380909
Standards:	B380810 (6F); B380830 (2B); B380850 (4D); B380870 (5E); B380890 (7G); B380910 (3C)
Blanks:	B380796; B380816; B380836; B380856; B380876; B380896; B380916

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
103.63	338.7	48.9	004.7	005.7
134.11	344.4	49.0	010.4	011.4
166.12	340.8	50.4	006.8	007.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1 | DATE: July 8-10, 2005 | PAGE 1 of 6

DRILL HOLE # : DG05-293C

FeOx: 0 = Unoxidized, 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered
Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-15.24	0.00	15.24	Casing. 1% recovery, lim on MSED.						
1	15.24-19.81	15.24	16.76	Very poor recovery. 10cm of QZZ, lim stained.						
1		16.76	18.29	Sand, gravel, pebbles. Diverse lithology, likely bedload from creek.	3			1		
1		18.29	19.81	Diverse lithology, core is composed of rounded section of boulders/float, bedload. Lim pervasive & staining.	2					
90	19.81-21.34	19.81	21.34	Broken QZZ. Lim staining on faces. Trace dissem aspy found on faces.	2					
1	21.34-22.86	21.34	22.86	Rounded pebbles-cobbles of diverse lithology mixed w/ broken QZZ & MSEDs. Lim staining on faces. Foliation where visible @ 50-55°.	2					
90	22.86-36.58	22.86	35.05	Broken QZZ w/ lim staining on frac faces. Foliation where visible 55-60°. At 24.38-28.96m: dissem py & aspy. @ 27.83m: Euhedral aspy on faces. @ 28.89m: 7cm sandy gouge. No contact angles.	2					
90		35.05	36.58	QZZ--minor lim staining, absent by end of interval.	1					
80	36.58-59.44	36.58	48.23	Silicious MSED. Colour is light to dark grey, core is broken. Foliations @36.58m: 60-65°- diss aspy; @38.10m: 65-70°- diss aspy; @39.62m: 60-65°- diss aspy; @ 42.67m: 50-55°; @ 44.20m: 55-60°; @ 45.72m: 55-60°; @ 47.24m: 55-60° - diss aspy. Very few vns in section, sulphides mostly dissem or found as euhedral crystals on frac faces.						
80		48.23	55.46	Silicious MSED. Colour varies from light to dark grey. Lim staining returns on faces. Foliation @ 48.23m: 60-65°; @ 48.77m: 65-70°--py on frac face; @ 50.29m: no visible foliations; @ 51.83m: 65-70°; @ 53.36m: no visible foliation; @ 54.86m: no visible foliation--diss py.	2					
80		55.46	56.39	Core is light grey green, heavily lim stained, easily scratchable, no visible foliation.						
80		56.39	57.91	Light brown to light grey MSED. Fracs are filled w/ ox'd py, filling 3% of core. The fracs & vnlets crosscut, as well as follow the foliation. There is no preferred angle (high or low). Foliation @ 55-60°, lim on frac faces.	2	1			1	
80		57.91	59.44	Silicified MSED. Light to dark grey. Foliation @ 55-60°. Low angle (165-170°) carb vns crosscut foliation. Lim on frac faces.	2	1			1	
1	59.44-60.96	59.44	60.96	Broken, rounded pc's of diverse lithology. Possibly came from higher in hole.	2	1	1	1	1	
80	60.96-102.28	60.96	65.00	Light grey MSED. Core is broken, and frac faces covered w/ lim. Foliation @ 60.96m: 55-60°; @ 62.48m: 55-60°; @ 64.01m: 35-40°; @ 64.21m: 45-50°. at 63.31m: 22cm of breccia. Foliation uphole @ 35-40°, downhole @ 55-60°. Contact angles uphole @ 60°, downhole @ 30°. Clasts range from light grey to dark grey MSEDs & qtz. Foliation still visible in MSED clasts. Clast movement may indicate a normal fault (HW uphole), at a high angle ~80°, crosscuts foliation.	2	1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8-10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B380792	15.24	16.76	<0.005			VA05060560	1.52
0																						B380793	16.76	18.29	0.241			VA05060560	1.53
0																						B380794	18.29	19.81	0.165			VA05060560	1.52
1	1	3.0	3.0	90																		B380795	19.81	21.34	0.174			VA05060560	1.53
1	1	3.0	3.0	90																		B380796	BLANK		<0.005			VA05060560	
																						B380797	21.34	22.86	0.090			VA05060560	1.52
0																						B380798	22.86	24.38	0.021		broken into pc's	VA05060560	1.52
1	6	0.1											0.1									B380799	24.38	25.91	0.019		dissem aspy	VA05060560	1.53
0																						B380800	25.91	27.43	0.374		dissem aspy	VA05060560	1.52
3	6	0.1								0.1												B380801	27.43	28.96	0.845			VA05060560	1.53
2	6	0.2	0.4										1.0									B380802	27.43	28.96	0.636	DUP	broken veins	VA05060560	1.53
2	6	0.2	0.4										1.0									B380803	28.96	30.48	0.053			VA05060560	1.52
2	1	0.2	0.4	40																		B380804	30.48	32.00	0.040			VA05060560	1.52
0.2	1	0.2	0.4	40																		B380805	32.00	33.53	0.009			VA05060560	1.53
0																						B380806	33.53	35.05	0.007		broken	VA05060560	1.52
1	1	73.0											1.0									B380807	35.05	36.58	<0.005			VA05060560	1.53
3	1	0.2	0.6	60																		B380808	36.58	38.10	0.023		broken into pc's	VA05060560	1.52
1	1	4.0																				B380809	36.58	38.10	0.021	PD/CA		VA05060560	1.52
1	1	4.0																				B380810	STANDARD 6F		2.820	6F		VA05060560	
																						B380811	38.10	39.62	0.034			VA05060560	1.52
3	1	1.0	1.4	40	55								0.1									B380812	39.62	41.95	0.092		broken pc's	VA05060560	2.33
1	1																					B380813	41.95	42.67	0.008		broken pc's	VA05060560	0.72
	1	1.0																				B380814	42.67	44.20	0.009		dissem aspy & py	VA05060560	1.53
3	1	0.5	0.9	50																		B380815	44.20	45.72	0.254		dissem aspy & py	VA05060560	1.52
2	1	2.0	3.0	50																		B380816	BLANK		<0.005			VA05060560	
																						B380817	45.72	47.24	0.014		broken vns, diss py	VA05060560	1.52
	1																					B380818	47.24	48.23	0.036			VA05060560	0.99
1	1	3.0	3.0	60																		B380819	48.23	48.77	<0.005		vnlets	VA05060560	0.54
	3	0.1		10																		B380820	48.77	50.29	0.007		broken vns, diss py	VA05060560	1.52
1	1	1.0																				B380821	50.29	51.83	0.053		vnlets	VA05060560	1.54
	4	0.1		10																		B380822	50.29	51.83	0.038	DUP		VA05060560	1.54
	4	0.1		10																		B380823	51.83	53.36	<0.005			VA05060560	1.53
0																											broken		
	1	1.0																				B380824	53.36	54.86	<0.005		broken pc's	VA05060560	1.50
	1	1.0																				B380825	54.86	55.46	0.167		vnlets	VA05060560	0.60
	3	0.1	45.0																			B380826	55.46	56.39	0.259			VA05060560	0.93
0																						B380827	56.39	57.91	0.015		vnlets, no preferred orientation	VA05060560	1.52
	6	0.1								3.0												B380828	57.91	59.44	<0.005			VA05060560	1.53
3	6	0.1	0.3	20						0.1												B380829	57.91	59.44	<0.005	PD/CA		VA05060560	1.53
3	6	0.1	0.3	20						0.1												B380830	STANDARD 2B		3.430	2B		VA05060560	
																						B380831	59.44	60.96	0.024			VA05060560	1.52
0																						B380832	60.96	62.48	0.116			VA05060560	1.52
2	1	0.5	0.7	40						0.1												B380833	62.48	64.01	0.008			VA05060560	1.53
6	1	0.1	0.1	30						0.1												B380834	64.01	65.00	<0.005			VA05060560	0.99
2	1	0.2	0.4	40						0.1																			

DRILL LOG LEGEND P1	DATE: July 8-10, 2005	PAGE 3 of 6		
DRILL HOLE # : DG05-293C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		65.00	65.33	Graphitic MSED. Black color, greasy feel. Foliations are folded and fractured w/ offset dextrally. Vning is qtz/cb and contains 2% py. Foliation @ 40°.		1				
80		65.33	66.41	Silicified MSED. Light grey, lim on frac. Foliation @ 60° to CA.		1				
80		66.41	67.06	Clay gouge, black to dark grey. Greasy feel--graphitic. Clay is soft and moldable. Frags of parent rock found w/in--black MSEDs.		1				
80		67.06	70.10	Silicified MSED. Light to dark grey, core is broken. No lim present. Foliation @ 67.06m--55-60°; @ 68.58m--55-60°. Dissem py from 67.26-67.46m. End of HQ.		2				
80		70.10	83.82	Beginning of NQ core @ 70.10m. Reduction in core size required due to cave and clay. MSED--silicified. Light grey to dark grey color. Foliation is difficult to see. Foliation @ 70.10m: not visible; @ 71.63m: 60-65°; @ 73.15m: 55-60°; @ 74.68m: 60-65°; @ 76.20m: 65-70°; @ 77.72m: 60-65°; @ 79.25m: 40-45°; @ 80.77m: not visible; @ 82.30m: too broken to measure. At 76.30m: 15cm black core--graphitic.		1	1		1	
80		83.82	86.87	Clay gouge--grey. Qtz & MSED frags present. No contact angle.		1		4	1	
80		86.87	89.92	Light grey MSED and gouge. Contact w/ gouge (from previous interval) @ 5° from CA. Gouge continues at this angle until 88.42m. After 85.38m, core is broken and mixed w/ gouge. Unable to determine angles or position.		1		3	1	
80		89.92	92.96	Light grey MSED. Foliation is more pronounced. Core begins to darken to brown/violet color. Foliation @ 50-55°.						
80		92.96	102.21	Core is dark grey/brown/violet. Foliation @ 92.96m: core broken; @ 94.49m: core broken; @ 96.01m: 30-35°; @ 97.54m: 35-40°; @ 99.06m: 45-50°; @ 100.58m: 50-55°. Core shows boudins w/ increased strain. @ 96.01m: core shows more strain. Foliation is crenulated, growth of qtz eyes. @ 98.81m: 3cm clay gouge @ 55° to CA.						
80		102.21	102.28	3cm qtz vn w/ 20% aspy. Vn runs @ 30°--same as sulphide vnlets throughout core.						
25	102.28-103.63	102.28	103.63	Mafic intrusive--porphoritic plag phenocrysts, some calcite. Groundmass shows chl alt'n--diabase. Qtz/cb vnlets throughout.			2		1	
80	103.63-166.12	103.63	114.30	MSED--light to dark grey. Very few vns. Cb on frac faces and as vnlets. Boudins present, increased shear. Foliation @ 103.63m: 65-70°; @ 105.16m: 45-50°; @ 106.68m: 55-60°; @ 108.20m: 60-65°; @ 109.73m: 55-60°; @ 111.25m: 50-55°; @ 112.78m: 55-60°. At 105.02m: 7cm clay gouge @ 50°; @ 108.04m: 6cm clay gouge @ 50°, MSED frags; @ 108.14m: 6cm clay gouge @ 50° to CA--mica.		2	2	1	1	
80		114.30	123.44	Silicious MSED. Light grey to dark grey. Foliation difficult to see in light grey core. Foliation @ 114.30: 80-85°; @ 115.82m: 45-50°; @ 117.35m: 50-55°; @ 118.87m: 60-65°; @ 120.40m: 65-70°. Few qtz vns sheeted set @ 17.06m. 3-0.2cm vns crosscuts foliation.		1	2	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8-10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3									2.0												B380835	65.00	65.33	<0.005		irregular shape, no measurable angle.	VA05060560	0.33
																						B380836	BLANK		<0.005			VA05060560	
2	1	0.2	0.4	55		0.1	s															B380837	65.33	66.41	0.082			VA05062472	1.08
0																						B380838	66.41	67.06	0.024			VA05062472	0.65
1	1	0.2	0.2	5																		B380839	67.06	68.58	0.318			VA05062472	1.52
2	4	0.1	0.2	30																		B380840	68.58	70.10	0.046			VA05062472	1.52
0																						B380841	70.10	71.63	<0.005		very poor recovery	VA05062472	1.53
0																						B380842	70.10	71.63	0.005	DUP		VA05062472	1.53
1	1	2.0	2.0	65																		B380843	71.63	73.15	0.006			VA05062472	1.52
4	6	0.1	0.4	60						0.1								90.0				B380844	73.15	74.68	0.094			VA05062472	1.53
1	1	2.0	2.0	65																		B380845	74.68	76.20	0.007			VA05062472	1.52
1	1	2.0	2.0	70																		B380846	76.20	77.72	0.072			VA05062472	1.52
2	1	1.0	1.0	55									0.1									B380847	77.72	79.25	0.012			VA05062472	1.53
1	1	0.2	0.2	60																		B380848	79.25	80.77	<0.005			VA05062472	1.52
1	1	0.2	0.2	60																		B380849	79.25	80.77	<0.005	PD/CA		VA05062472	1.52
																						B380850	STANDARD 4D		0.434	4D		VA05062472	
2	1	3.0	3.2	60									0.1									B380851	80.77	82.30	<0.005			VA05062472	1.53
2.5	1	0.2	0.4																			B380852	82.30	83.82	<0.005		broken	VA05062472	1.52
																						B380853	83.82	85.34	<0.005		gouge	VA05062472	1.52
																						B380854	85.34	86.87	<0.005		gouge	VA05062472	1.53
3	3	0.1	0.3	10																		B380855	86.87	88.39	0.005		vnlets	VA05062472	1.52
																						B380856	BLANK		<0.005			VA05062472	
	3																					B380857	88.39	89.92	<0.005		broken vnlets	VA05062472	1.53
	3	0.1		55																		B380858	89.92	91.44	0.007			VA05062472	1.52
																						B380859	91.44	92.96	<0.005			VA05062472	1.52
4	6	0.1	0.4	60						1.0												B380860	92.96	94.49	0.013			VA05062472	1.53
1	1	0.5	0.5	80						1.0												B380861	94.49	96.01	<0.005			VA05062472	1.52
1	1	0.5	0.5	80						1.0												B380862	94.49	96.01	<0.005	DUP		VA05062472	1.52
	3	0.1		15																		B380863	96.01	97.54	<0.005			VA05062472	1.53
0																						B380864	97.54	99.06	<0.005			VA05062472	1.52
1	1	3.0	3.0	30																		B380865	99.06	100.58	<0.005			VA05062472	1.52
1	1	1.0	1.0	70																		B380866	100.58	102.21	<0.005			VA05062472	1.63
1	6	3.0	3.0	30		1.0	chl	3	0				20.0									B380867	102.21	102.28	4.640			VA05062472	0.07
6	3	0.1	0.6	20																		B380868	102.28	103.63	0.141			VA05062472	1.35
6	3	0.1	0.6	20																		B380869	102.28	103.63	0.148	PD/CA		VA05062472	1.35
																						B380870	STANDARD 5E		1.150	5E		VA05062472	
	1									0.1			10.0									B380871	103.63	105.16	0.918		irregular stringer, no discernable angle	VA05062472	1.53
	1									1.0												B380872	105.16	106.68	<0.005		broken pc's	VA05062472	1.52
1	1	2.0	2.0	40		1.0	chl	3	0		0.1											B380873	106.68	108.20	<0.005			VA05062472	1.52
	3	0.1		30																		B380874	108.20	109.73	0.043		vnlets	VA05062472	1.53
	3	0.1		30																		B380875	109.73	111.25	<0.005		vnlets	VA05062472	1.52
																						B380876	BLANK		<0.005			VA05062472	
4	1	0.2	0.8	80		2.0	s	4	0		0.1											B380877	111.25	112.78	<0.005			VA05062472	1.53
3	1	2.0	5.0	40		1.0	s	3	0	1.0			1.0									B380878	112.78	114.30	<0.005			VA05062472	1.52
2	4	0.2	4.0	10																		B380879	114.30	115.82	<0.005			VA05062472	1.52
3	1	0.2	0.6	30																		B380880	115.82	117.35	<0.005		crosscut foliation	VA05062472	1.53

DRILL LOG LEGEND P1

DRILL HOLE # : DG05-293C

DATE: July 8-10, 2005 PAGE 5 of 6

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		123.44	126.49	MSED light grey to brown/violet. Foliation @ 123.44m: 60-65°; @ 124.97m: 55-60°. Boudins still present. Cb vns present.		2	2	1	2	
80		126.49	131.06	Silicified MSED. Light grey to brown. Foliation more distinct in darker coloured core. Qtz fills irregular voids btwn foliations. Foliation @ 126.49m: 55-60°; @ 128.02m: 50-55°; @ 129.54m: 55-60°.		1	1	1	1	
80		131.06	132.59	MSED--easily scratchable. Foliation @ 60-65° to CA. Vns btwn foliation.		2	2	1	1	
80		132.59	134.11	Silicious MSED. Foliation difficult to see. Less alt'n, vns at low angles to CA.			1		1	
80		134.11	138.68	MSED--easily scratchable. Foliation @ 134.11m: 45-50°; @ 135.64m: 30-35°; @ 137.16m: 40-45°. Cb vns crosscut foliation, boudins still present.		2	2	1	1	
80		138.68	144.78	MSED--easily scratchable. Foliation @ 138.68m: 45-50°; @ 140.21m: 50-55°; @ 141.73m: 60-65°; @ 143.26m: 55-60°. Boudins no longer present.						
80		144.78	149.35	Silicious MSED interbedded w/ softer, more alt'd MSEDs. Silicious bands are light grey in color, and foliation is difficult to see. The remaining MSEDs are dark grey w/ highly visible foliation. Vns in this type follow foliation. Low angle qtz/cb vnlets cut all core. foliation @ 144.78m: 55-60°; @ 146.30m: 55-60°; @ 147.83m: 55-60°.		2	2	1	1	
80		149.35	152.40	Silicious MSED. Light to dark grey color. Foliation is difficult to distinguish in light grey MSED. Foliation @ 149.35m: 55-60°; @ 150.88m: 55-60°. Vns follow foliations.		1	1		1	
80		152.40	155.45	Dark grey MSED, easily scratched. Vns are irregular but follow foliation. Foliation @ 152.40m: 50-55°; @ 153.92m: 50-55°.		2	2	1	1	
80		155.45	158.03	Silicious MSED. Light to dark grey color. Foliation is difficult to distinguish in light grey MSED. Foliation @ 155.45m: 60-65°; @ 156.97m: 55-60°. @ 157.17m: 9cm qtz vns w/ 10% massive py in grey qtz. Follows foliation @ 55°. @157.32m: 25cm of qtz vns, follow foliation, but no distinction can be made where vns start and end. Vns interlaced w/ MSEDs. Massive po present--5%. Follow foliation.		1	1		1	
80		158.03	166.12	MSED. Soft, easily scratchable. Dark grey green to grey. Very few vns present. Those present are 2-3cm and follow foliation. Foliation @158.50m: 55-60°; @160.02m: 55-60°; @161.54m: 60-65°; @ 163.07m: 55-60°; @ 164.59m: 55-60°. Carb increases.		1	2	1	2	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date:_____July 8-10th, 2005_____

LOGGED BY:_____Terry Croteau_____

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						SELVAGES				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6	30						0.1												B380881	117.35	118.87	<0.005			VA05062472	1.52
3	1	0.2	0.6	30						0.1												B380882	117.35	118.87	<0.005	DUP		VA05062472	1.52
0																						B380883	118.87	120.40	<0.005		recovery v.poor	VA05062472	1.53
	3			50																		B380884	120.40	121.92	0.011		vnlets	VA05062472	1.52
1	1	1.0	1.0	55		0.2	s	4	0													B380885	121.92	123.44	<0.005		btwn foliation	VA05062472	1.52
3	1	1.0	1.4	40						0.1												B380886	123.44	124.97	<0.005		btwn foliation	VA05062472	1.53
3	4	0.2	0.6	30																		B380887	124.97	126.49	<0.005		crosscut foliation	VA05062472	1.52
4	1																					B380888	126.49	128.02	0.013		irregular fill btwn foliation	VA05062472	1.53
4	1																					B380889	126.49	128.02	0.011	PD/CA		VA05062472	1.53
																						B380890	STANDARD 7G		4.560	7G		VA05062472	
	3			10																		B380891	128.02	129.54	0.008		vnlets	VA05062472	1.52
4	1	2.0	6.0	60																		B380892	129.54	131.06	0.008		crosscuts	VA05062472	1.52
6	1	3.0	9.0	50		3.0	chl	3	0	0.1												B380893	131.06	132.59	0.009			VA05062472	1.53
2	1	3.0	4.0	50		2.0	chl	2	0													B380894	132.59	134.11	0.010			VA05062472	1.52
4	1	1.0	3.0	50							0.1											B380895	134.11	135.64	<0.005			VA05062472	1.53
																						B380896	BLANK		<0.005			VA05062472	
4	1	2.0	3.0	70	60																	B380897	135.64	137.16	<0.005			VA05062472	1.52
1	4	0.5	0.5	20																		B380898	137.16	138.68	<0.005		follows foliation	VA05062472	1.52
3	1	1.0	2.5	50																		B380899	138.68	140.21	<0.005			VA05062472	1.53
4	1	1.0	2.5	50							0.1											B380900	140.21	141.73	<0.005			VA05062472	1.52
2	1	1.0	1.5	60																		B380901	141.73	143.26	<0.005			VA05062472	1.53
2	1	1.0	1.5	60																		B380902	141.73	143.26	<0.005	DUP		VA05062472	1.53
	4			45																		B380903	143.26	144.78	0.011		vnlets crosscut foliation	VA05062472	1.52
	4			30																		B380904	144.78	146.30	<0.005		vnlets crosscut foliation	VA05062472	1.52
	4			30																		B380905	146.30	147.83	<0.005		vnlets crosscut foliation	VA05062472	1.53
1	1	1.0	1.0	40																		B380906	147.83	149.35	<0.005			VA05062472	1.52
1	3	0.5	0.5	40																									
2	1	0.5	0.7	65		4.0	q	5	0													B380907	149.35	150.88	0.006			VA05062472	1.53
3	1	10.0	12.0	60							1.0											B380908	150.88	152.40	<0.005			VA05062472	1.52
3	1	10.0	12.0	60							1.0											B380909	150.88	152.40	<0.005	PD/CA		VA05062472	1.52
																						B380910	STANDARD 3C		0.092	3C		VA05062472	
2	1	0.2	0.4	70																		B380911	152.40	153.92	<0.005			VA05062472	1.52
2	1	1.0	2.0	55	65					0.1												B380912	153.92	155.45	<0.005			VA05062472	1.53
2	1	1.5	2.0	70																		B380913	155.45	156.97	<0.005			VA05062472	1.52
5	1	25.0	40.0	55						10	5.0											B380914	156.97	158.03	0.112			VA05062472	1.06
1	1	1.0	1.0	70																		B380915	158.03	158.50	<0.005			VA05062472	0.47
																						B380916	BLANK		<0.005			VA05062472	
1	1	1.0	1.0	70							0.1											B380917	158.50	160.02	<0.005			VA05062472	1.52
1	1	0.5	0.5	70																		B380918	160.02	161.54	<0.005			VA05062472	1.52
2	1	6.0	7.0	60						0.1												B380919	161.54	163.07	<0.005			VA05062472	1.53
1	3	0.2	0.2	20																							crosscuts foliation		
5	1	6.0	8.0	60																		B380920	163.07	164.59	0.006			VA05062472	1.52
4	1	0.1	0.4	40																		B380921	164.59	166.12	<0.005			VA05062472	1.53
4	1	0.1	0.4	40																		B380922	164.59	166.12	<0.005	DUP		VA05062472	1.53
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-294C

PROJECT: Dublin Gulch - 1735

DATE STARTED: 15-Jul-05	DATE COMPLETED: 18-Jul-05
LOGGED BY: Terry Croteau	
CONTRACTOR: Britton Brothers	

GROUND ELEVATION: 833m

BEARING: 000 DIP: -50°

COORD SYSTEM: NAD 27: EASTING: 459080 NORTHING: 7100730

COORD SYSTEM: NAD 83: EASTING: 458961 NORTHING: 7100915

NAD 27 (CORRECTED for historic grid): EASTING: 459050 NORTHING: 7100740

SECTION LINE (historic grid): 459050E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 52 ft, 15.85m

Deviation:

Casing: 52 ft, 15.85m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
4.57	13.72	OVB; Variable lithologies, coarse gravel
13.72	44.88	OVB; Breccia with fault gouge, highly alt'd
44.88	95.31	MSED
95.31	98.63	QZZ
98.63	155.63	MSED
155.63	157.17	QZZ
157.17	191.82	MSED
191.82	198.60	QZZ
198.60	234.70	MSED
234.70	237.00	HFLS
237.00	240.60	QZZ
240.60	268.22	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B380923 to B381004

Requisition #: MASP448STRGOL.05Q — Date Shipped: 22-Jul-05

Lab Record #: VA05062473, VA05063074 (3) — Date Received: 27-Jul-05, 29-Jul-05

Sample Sequence: B381005 to B381110

Requisition #: MASP448STRGOL.05Q — Date Shipped: 17-Jul-05

Lab Record #: VA05064959 — Date Received: 9-Aug-05

Sample Sequence: B381111 to B381180

Requisition #: MASP448STRGOL.05Q — Date Shipped: 17-Jul-05

Lab Record #: VA05066289 — Date Received: 12-Aug-05

Duplicates:	B380942, B380962, B380982,B381002, B381022, B381042, B381062, B381082, B381102, B381122, B381142, B381162
Preparation Duplicate/ Check Assay:	B380929, B380949, B380969, B380989,B381009, B381029, B381049, B381069, B381089, B381109, B381129, B381149, B381169,
Standards:	B380930 (2B), B380950 (6F), B380970 (5E), B380990 (3C), B381010 (6F), B381030 (4D), B381050 (1A), B381070 (3C), B381090 (2B), B381110 (5E), B381130 (4D), B381150 (5E), B381170 (3C)
Blanks:	B380936, B380956, B380976, B380996, B381016, B381036, B3810456, B381076, B381096, B381116, B381136, B381156, B381176

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	DIP (+ 27 Corr)
60	002.5	-50.5	028.5	029.5
121.92	007.5	-52.3	033.5	034.5
182.88	009	-55.3	035	036
268.21	018.7	-57.9	044.7	045.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1 | DATE: July 16-28, 2005 | PAGE 1 of 12

DRILL HOLE # : DG05-294C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 4.57			Casing - No Recovery						
1	4.57 - 13.72	4.57	10.67	OVB: Core consists of GND, MSED, QZZ fragments. GND is solid, core with intervals of gravel to cobble size.	1					
1		10.67	13.72	Clay gouge; Clay mixed with pebble and gravel sized pieces with diverse lithology; Contact with breccia at 56° TCA; 3m sample, very poor recovery.						
1	13.72 - 44.88	13.72	15.24	Beginning of a 24.71m zone of breccia and gouge; Cb alt'n is dominant; Limonite is pervasive in the gouge; Recovery is poor. 40cm of breccia contact with MSED @ 30° TCA; Clast size ranges from 1mm to 1cm, with 80% from 2-.5cm; They appear to be unsorted and oriented to follow the 30° angle of the MSED contact; Py found in matrix					1	
1		15.24	16.76	Clay gouge; Hematite is pervasive; Original foliation preserved; At 15.26m, 55° TCA; Dark grey MSED frags present; Contact with breccia not present	3	2		4		
1		16.76	19.81	Breccia and clay gouge; Clasts are larger and sub-angular; Py fills fractures; No contact angle; Gouge at 18.09m; Pervasive limonite; Relict brecciated vein 3cm wide at 18.11m; At 19.51m returns to breccia.	3			3	1	
1		19.81	22.56	Breccia; Carb alt'n increases; Matrix now contains carbonate; Quartz veins are fractured and filled with carbonate; Clasts in the breccia are larger, up to 4cm with 80% 0.4 to 1.5cm; Clasts appear to follow 40° angle TCA; Slip direction appears normal.	3			3	3	
1		22.56	23.42	Breccia is black and shows intense clay alteration; No limonite present; At 23.09m, a 5cm qtz/cb vein at 85° TCA; Most veins in section fragmented and offset; Fractures filled with carbonate				3	1	
1		23.42	25.91	Core is much less brecciated with original foliation visible. At 24.68m, foliation at 30° TCA; Carbonate alteration is less intense; Pyrite visible in fractures in areas of clay alteration; At 25.31m, 44cm of clay alteration and gouge; Contact with breccia at 50° TCA; Minor limonite staining on fractured quartz veins.				3	1	
1		25.91	34.56	Breccia: Carbonate alteration dominant in matrix; Clasts range in size from 0.1cm to >5cm, with an average size of 1.5cm.; At 27.43m tension gashes filled with fragments and quartz and carbonate cement; Extensional - Normal fault?; Limonite is pervasive in gouge at 28.46m, 32.4m, 32.2m and 33.73m; At 37.91m Tension gashes and movement of clasts indicate extensional movement, likely high angle - gashes at 75° TCA.	1	1		2	2	
1		34.56	38.43	Breccia and gouge; Breccia is composed of smaller clasts 0.1 to 0.3cm with 80% 0.5cm; Gouge is dark grey, greasy feel, graphitic; Original lineation is visible at 36.68m; Foliation at 50° to 55° TCA; Gouge contains qtz and MSED frags; At 33.46m = 20cm clay gouge; At 35.46m = 57cm clay gouge.	1	1		2	2	
1		38.43	44.88	Fault Zone; Dark grey; Contact with breccia at 20° TCA; Qtz eyes and MSED porphyroclasts; At 38.25m = Most intense deformation, 80cm dark grey, graphitic with abundant qtz eyes. Porphyroclasts contain disseminated pyrite; Contact is breccia at 20° TCA; Contact angles between breccia/fault/gouge at 39.24m at 40° TCA; At 41.15m, at 45° TCA. At 42.67m, at 56° TCA; At 44.2m, at 50° TCA; Clay alteration tends to follow relic foliation angles at 60°.	1	1		2	2	
80	44.88 - 95.31	44.88	48.77	MSED and gouge/heavy clay alteration along foliations; Carbonate alteration present mostly on fracture faces; Contact with fault zone at 60° TCA.; Foliation at 44.88m, at 25-30° TCA; At 45.72m foliation at 35-40° TCA; At 47.24m foliation at 45-50° TCA.		1		4	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 6 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
0																						B380923	4.57	6.10	<0.005			VA05062473	1.53
																						B380924	6.10	7.62	<0.005			VA05062473	1.52
																						B380925	7.62	9.14	<0.005			VA05062473	1.52
																						B380926	9.14	10.67	<0.005			VA05062473	1.53
																						B380927	10.67	13.72	0.01		3 m sample	VA05062473	3.05
0										0.1												B380928	13.72	15.24	<0.005		Py found in mtx	VA05062473	1.52
0										0.1												B380929	13.72	15.24	<0.005	PD/CA		VA05062473	1.52
																						B380930	STANDARD 2B		3.02	2B		VA05062473	
0																						B380931	15.24	16.76	0.01			VA05062473	1.52
0																						B380932	16.76	18.29	<0.005			VA05062473	1.53
0																						B380933	18.29	19.81	0.01			VA05062473	1.52
1	4	0.2	0.2	85																		B380934	19.81	21.34	0.02			VA05062473	1.53
0																						B380935	21.34	22.56	<0.005			VA05062473	1.22
0																						B380936	BLANK		<0.005			VA05062473	
3	3	5.0	8.0	85																		B380937	22.56	23.42	<0.005			VA05062473	0.86
2	3	4.0	4.5	70																		B380938	23.42	24.55	<0.005			VA05062473	1.13
3	3	1.0	2.5	55	75					1.0												B380939	24.55	25.91	<0.005			VA05062473	1.36
3	6	0.1	0.3	60						1.0												B380940	25.91	27.43	<0.005			VA05062473	1.52
0																						B380941	27.43	28.96	<0.005			VA05062473	1.53
0																						B380942	27.43	28.96	<0.005	DUP		VA05062473	1.53
3	6	0.1	0.3	60						1.0												B380943	28.96	30.48	<0.005			VA05062473	1.52
0																						B380944	30.48	32.00	<0.005			VA05062473	1.52
0																						B380945	32.00	33.53	<0.005			VA05062473	1.53
4	6	0.1	0.4	60						1.0												B380946	33.53	34.56	<0.005			VA05062473	1.03
0																						B380947	34.56	35.05	<0.005			VA05062473	0.49
0																						B380948	35.05	36.58	<0.005			VA05062473	1.53
0																						B380949	35.05	36.58	<0.005	PD/CA		VA05062473	1.53
																						B380950	STANDARD 6F		2.54	6F		VA05062473	
1	1	1.0																				B380951	36.58	38.10	<0.005		Brcc'd. Diss py	VA05062473	1.52
0																						B380952	38.10	38.43	<0.005			VA05062473	0.33
																						B380953	38.43	39.62	<0.005			VA05062473	1.19
0																						B380954	39.62	41.15	<0.005			VA05062473	1.53
0																						B380955	41.15	42.67	<0.005			VA05062473	1.52
																						B380956	BLANK		<0.005			VA05062473	
0																						B380957	42.67	44.20	0.01			VA05062473	1.53
0																						B380958	44.20	44.88	0.03			VA05062473	0.68
0																						B380959	44.88	45.72	0.01			VA05062473	0.84
2	1	2.0	0.4	45																		B380960	45.72	47.24	<0.005			VA05062473	1.52
2	3	1.0	1.4	45																		B380961	47.24	48.77	<0.005			VA05062473	1.53
2	3	1.0	1.4	45																		B380962	47.24	48.77	<0.005	DUP		VA05062473	1.53

DRILL LOG LEGEND P1	DATE: July 16-28, 2005	PAGE 3 of 12	
DRILL HOLE # : DG05-294C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		48.77	53.34	MSED (phyllitic); Dark grey to reddish brown bands, soft and easy to scratch; Several sections contain more siliceous MSED between foliations, but showing no foliation themselves. These sections are a maximum of 0.8cm long. Foliations at 48.77m, at 47-50° TCA; At 50.29m, at 45-50° TCA; at 51.82m, at 35-40° TCA.		1	1	1	2	3
80		53.34	54.86	MSED; Intense clay alteration between foliations; Unaltered areas are more siliceous and show no visible foliations; At 53.34m 10cm of sticky, malleable clay, grey in color.		1		4	2	
80		54.86	57.35	MSED; Brown to grey-blue in color; Very strong effervescence between foliations with HCL; Foliations at 55-60°.				2	5	
80		57.35	57.91	MSED; Possibly carbonaceous; Core is black and very fine laminations present; Minor clay alteration; Foliation at 75° TCA.				2		
80		57.91	59.44	QZZ and Argillite (MSED); No foliation in QZZ or arg, Contacts at 30° and 75°; 75° more common; Cb veins abundant at 10-30°.				2	2	
80		59.44	62.48	MSED and Argillite; Core is dark grey to black; MSED shows intense alteration, much less in Argillite; Argillite is carbonaceous; At 60.96m, 25cm of siliceous MSED; Foliation where visible is 55° to 60° TCA.				4		
80		62.48	70.48	Siliceous MSED 90% and QZZ 10%; MSED is light brown to grey; QZZ contact angles follow foliations, but contain no visible foliation; Foliations at 62.48m = 75-80° TCA; 64.01 m = 80-85° TCA; 65.53m = 70-75° TCA; 67.06m = 80-85° TCA; 68.58m = 70-75° TCA; 70.10m = 70-75° TCA; MSED is phyllitic; At 62.48m = 9cm sandy gouge - No contact; At 63.92m = 8cm clay gouge = no contact; At 69.90m = 9cm sandy gouge at 75° TCA				2	1	
80		70.48	78.58	QZZ (MSED); QZZ with interbedded siliceous MSED; Foliation is visible in the MSED at 65-70° TCA; There is an increase in the qtz vein size and intensity; They appear in the MSED and follow foliation; Trace pyrrhotite present in veins; At 78.52m a 0.2 cm sulphide vein with 40% pyrrhotite.			2	1		
80		78.58	83.82	Siliceous MSED; Qtz veins still present; 2cm-7cm wide; Foliation at 78.58m = 60-65° TCA; At 79.25m = 55-60° TCA; At 80.77m = 55-60° TCA; At 82.3m = 55-60° TCA; Core is light grey, veins between foliations			1	1		
80		83.82	89.29	MSED; Moderate to intense clay alteration between foliations; Foliations at 83.82m at 65-70° TCA; At 85.39m at 65-70° TCA; At 86.62m at 55-60° TCA (crenulation cleavage); Becomes parallel TCA at 87.99-88.39m; At 88.39m is 70-72° TCA; At 85.72-86.62m = 0.2cm py vn running parallel TCA.		2	2	3		
80		89.29	95.31	MSED; Dark Grey to black, phyllitic; Foliation at 89.29m = 50-52° TCA; At 89.92m = 55-60° TCA; At 91.44m = 50-55° TCA; 92.96m = 50-52° TCA; 94.49m = 55-60° TCA; Qtz veins found between foliations; Low angle carbonate veins common (10-30° TCA)						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	1.5	1.5	55																		B380963	48.77	50.29	<0.005			VA05062473	1.52
3	1	0.2	0.6	50																		B380964	50.29	51.82	<0.005			VA05062473	1.53
2	3	0.5	1.0	35	10																	B380965	51.82	53.34	<0.005			VA05062473	1.52
1	3	0.5	0.5	50																		B380966	53.34	54.86	0.01			VA05062473	1.52
4	4	1.0	1.6	30																		B380967	54.86	56.39	<0.005			VA05062473	1.53
	4			30																		B380968	56.39	57.35	<0.005		Veinlets	VA05062473	0.96
	4			30																		B380969	56.39	57.35	<0.005	PD/CA		VA05062473	0.96
																						B380970	STANDARD 5E		1.43	5E		VA05062473	
0																						B380971	57.35	57.91	<0.005			VA05062473	0.56
1	1	2.5	2.5	50						1.0												B380972	57.91	59.44	<0.005		Min'n in clay alt'n surrounding the vein	VA05062473	1.53
2	4			60																		B380973	59.44	60.96	<0.005		Veinlets cross cut foliation	VA05062473	1.52
2	4																					B380974	60.96	62.48	<0.005			VA05062473	1.52
3	4	1.0	4.0	60																		B380975	62.48	64.01	<0.005			VA05062473	1.53
																						B380976	BLANK		<0.005			VA05062473	
	4			10	30																	B380977	64.01	65.53	<0.005		Veinlets	VA05062473	1.52
	4			20	30																	B380978	65.53	67.06	<0.005		Veinlets	VA05062473	1.53
2	4	0.1	0.2	30	20																	B380979	67.06	68.58	<0.005		Veinlets	VA05062473	1.52
3	4	0.1	0.3	20	25																	B380980	68.58	70.10	<0.005		Veinlets	VA05062473	1.52
	4																					B380981	70.10	70.48	0.04		Veinlets follow foliation	VA05062473	0.38
	4																					B380982	70.10	70.48	<0.005	DUP		VA05062473	0.38
0																						B380983	70.48	71.63	0.01			VA05062473	1.15
2	1	0.3	0.6	70						0.1												B380984	71.63	73.15	<0.005			VA05062473	1.52
	4																					B380985	73.15	74.68	<0.005		Veinlets follow fractures	VA05062473	1.53
1	3	0.1	0.1	40																		B380986	74.68	76.20	<0.005			VA05062473	1.52
6	1	7.0	13.5	80																		B380987	76.20	77.72	0.01			VA05062473	1.52
1	6	0.2	0.2	65							40.0											B380988	77.72	78.58	<0.005			VA05062473	0.86
1	6	0.2	0.2	65							40.0											B380989	77.72	78.58	0.01	PD/CA		VA05062473	0.86
																						B380990	STANDARD 3C		0.09	3C		VA05062473	
2	1	0.2	0.4	80																		B380991	78.58	79.25	<0.005			VA05063074	0.67
4	1	7.0	9.5	70																		B380992	79.25	80.77	0.01			VA05063074	1.52
3	1	5.0	8.0	75							3.0	0.1						40.0				B380993	80.77	82.30	0.01			VA05063074	1.53
2	1	6.0	6.5	70									0.1					90.0				B380994	82.30	83.82	0.25			VA05063074	1.52
0																						B380995	83.82	85.39	0.17			VA05062473	1.57
																						B380996	BLANK		<0.005			VA05062473	
0																						B380997	85.39	85.72	0.01			VA05062473	0.33
1	6	0.2	0.2	0	5					30.0												B380998	85.72	86.62	0.64			VA05062473	0.90
	1	0.2																				B380999	86.62	88.39	<0.005		Broken pieces	VA05062473	1.77
	1	1.0									0.1											B381000	88.39	89.29	<0.005		Quartz eyes and broken pieces	VA05062473	0.90
1	1	1.0	1.0	50									0.1									B381001	89.29	89.92	<0.005			VA05062473	0.63
1	1	1.0	1.0	50									0.1									B381002	89.29	89.92	<0.005	DUP		VA05062473	0.63
3	1	0.5	0.9	70																		B381003	89.92	91.44	<0.005			VA05062473	1.52
3	1	0.2	0.6	55																		B381004	91.44	92.96	<0.005		Irregular shape btw fol	VA05062473	1.52
1	1	0.2	0.2	25																		B381005	92.96	94.49	<0.005			VA05064959	1.53
0																						B381006	94.49	95.31	<0.005			VA05064959	0.82

DRILL LOG LEGEND P1	DATE: July 16-28, 2005	PAGE 5 of 12	
DRILL HOLE # : DG05-294C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70	95.31 - 98.63	95.31	98.63	QZZ; Light grey coloured, highly fractured; Hosts several large quartz veins (3-10cm); Veins are also highly fractured or broken; Trace to 1% oxidized pyrite found on fracture faces; Fracture angles varied 30-50°, crosscut by 150-165°.						
80	98.63 - 155.63	98.63	99.54	MSED: Intense clay and sericite alteration of MSED; No visible foliation angles; Unaltered MSED fragmented into gravel sized pieces, phyllitic; No visible foliation.		2		3		
80		99.54	102.11	MSED: Light to dark grey, phyllitic; Foliation at 99.54m = 50-52°; At 100.58m = 40-42° TCA; At 100.58m, 12cm argillite before change in foliation angle		1		1		
80		102.11	113.30	MSED: Core is soft easily scratchable; phyllitic; dark grey color. Foliations: at 102.11m = 55-60° TCA; At 103.63m = 45-50° TCA; At 105.16m = 40-45° TCA; At 106.68m = 45-50° TCA; At 108.2m = 45-50° TCA; At 109.73m = 45-50° TCA; At 111.25m = 45-50° TCA; 112.78m = 45-50° TCA: Quartz veins between foliations. The number of carb veinlets are reduced.		2	2	2	1	
80		113.30	115.82	Siliceous MSED: Light grey color; Increase in qtz and carb veins over interval; Qtz veins follow foliations where visible; Carb veinlets crosscut foliation at 113.3m = 40-45°; At 114.3m = 45-50° TCA						
80		115.82	118.87	MSED Light to dark grey; Phyllitic Qtz/Cb veins follow foliations; Cb veins crosscut foliations at 115.82m = 50-52° TCA; At 117.35m = 35-40° TCA; Clay alteration is increased after 117.35m		3	2	2	1	
80		118.87	121.92	MSED light grey-green; Chl alteration dominant, but sericite and clay still present; Cb veins continue to crosscut foliation; Foliation at 118.87m = 70-75°; At 120.40m = 65-70° TCA; 121.92m = 40-45° TCA		2	3	2	1	
80		121.92	122.47	Silicified MSED with crosscutting qtz veinlets and sulphide veins; Cb veinlets present.					2	
80		122.47	128.02	MSED: Intense clay alteration, light to dark grey color; Quartz between foliation; Foliation at 121.92m = 35-40° TCA; At 123.44m = 40-45° TCA; At 124.97m = 45-50° TCA; At 126.49m = 50-55° TCA; At 125.34m = 40cm clay gouge contains remnant MSED frags; At 127.22m = 60cm clay gouge with remnant MSED frags.		2	1	3	1	
80		128.02	129.94	MSED: Clay alteration greatly reduced; Chlorite alteration increased on fractures; Carbonate veins at low angle, cross cut foliation; Foliation at 128.02m = 35-40° TCA; At 129.54m = 40-45° TCA.		1	2	2	1	
80		129.94	132.28	Argillite (MSED): Dark grey, no foliation; Cb veinlets abundant.						
80		132.28	134.11	MSED: Dark grey-brown phyllitic; Fewer Cb veins/veinlets; Foliation at 132.28m = 85-90° TCA; At 132.59m = 45-50° TCA.		1	2		1	
80		134.11	135.64	Siliceous MSED: Dark grey-black; Qtz veins follow foliation; Cb altered and veining greatly reduced; Foliation at 60° TCA.						
80		135.64	141.23	MSED: Dark grey to black; Cb veinlets almost completely absent: Qtz veins between foliations; Po appears in veins; Foliations...At 135.64m = 55-60° TCA; At 137.16m = 50-55° TCA; At 138.68m = 55-60° TCA; At 140.61m = 40-42° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 6 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
0																						B381007	95.31	96.01	0.02			VA05064959	0.70
6	1	3.0	13.5	30									0.1					95.0				B381008	96.01	97.54	0.01			VA05064959	1.53
6	1	3.0	13.5	30									0.1					95.0				B381009	96.01	97.54	0.04	PD/CA		VA05064959	1.53
																						B381010	STANDARD 6F		2.88	6F		VA05064959	
0																						B381011	97.54	98.63	0.01			VA05064959	1.09
0																						B381012	98.63	99.06	0.07			VA05064959	0.43
0																						B381013	99.06	99.54	<0.005			VA05064959	0.48
0																						B381014	99.54	100.58	<0.005			VA05064959	1.04
2	1	0.2	0.4	55																		B381015	100.58	102.11	<0.005			VA05064959	1.53
																						B381016	BLANK		<0.005			VA05064959	
1	1	2.0	2.0	50									2.0									B381017	102.11	103.63	0.20			VA05064959	1.52
0																						B381018	103.63	105.16	<0.005			VA05064959	1.53
1	1	1.0	1.0	40									0.1									B381019	105.16	106.68	<0.005			VA05064959	1.52
3	1	3.0	4.0	60									0.1									B381020	106.68	108.20	<0.005			VA05064959	1.52
2	3	1.0	1.5	35																		B381021	108.20	109.73	<0.005			VA05064959	1.53
2	3	1.0	1.5	35																		B381022	108.20	109.73	<0.005	DUP		VA05064959	1.53
3	1	2.0	5.0	50																		B381023	109.73	111.25	0.02			VA05064959	1.52
2	3	2.0	3.0	50						3.0												B381024	111.25	112.78	0.04			VA05064959	1.53
0																						B381025	112.78	113.30	<0.005			VA05064959	0.52
2	4	0.2	0.4	50																		B381026	113.30	114.30	0.02			VA05064959	1.00
1	1	2.0	2.0	45																		B381027	114.30	115.82	0.01			VA05064959	1.52
	4			175	180																						Veinlets cross cut foliation		
																						B381028	115.82	117.35	0.01			VA05064959	1.53
																						B381029	115.82	117.35	0.01	PD/CA		VA05064959	1.53
																						B381030	STANDARD 4D		0.45	4D		VA05064959	
																						B381031	117.35	118.87	<0.005			VA05064959	1.52
	3			170	180																	B381032	118.87	120.40	0.01		Veinlets low angle crosscut	VA05064959	1.53
	3			170	180																	B381033	120.40	121.92	0.02		Veinlets low angle crosscut	VA05064959	1.52
4	1	5.0	9.0	45																		B381034	121.92	122.47	0.01			VA05064959	0.55
3	6	1.0	1.7	135									40.0						90.0										
0																						B381035	122.47	123.44	0.02			VA05064959	0.97
																						B381036	BLANK		<0.005			VA05064959	
0																						B381037	123.44	124.97	<0.005			VA05064959	1.53
1	1	2.5	2.5	45																		B381038	124.97	126.49	<0.005			VA05064959	1.52
0																						B381039	126.49	128.02	0.06			VA05064959	1.53
3	4	0.2	0.6	10	30																	B381040	128.02	129.54	<0.005			VA05064959	1.52
1	3	1.0	1.0	75																		B381041	129.54	129.94	<0.005			VA05064959	0.40
1	3	1.0	1.0	75																		B381042	129.54	129.94	<0.005	DUP		VA05064959	0.40
0																						B381043	129.94	130.30	<0.005			VA05064959	0.36
0																						B381044	130.30	131.06	<0.005			VA05064959	0.76
0																						B381045	131.06	132.28	<0.005			VA05064959	1.22
0																						B381046	132.28	132.59	<0.005			VA05064959	0.31
2	4	1.0	1.5	40																		B381047	132.59	134.11	<0.005			VA05064959	1.52
2	1	1.0	1.5	55																		B381048	134.11	135.64	<0.005			VA05064959	1.53
2	1	1.0	1.5	55																		B381049	134.11	135.64	<0.005	PD/CA		VA05064959	1.53
																						B381050	STANDARD 1A		0.80	1A		VA05064959	
0																						B381051	135.64	137.16	<0.005			VA05064959	1.52

DRILL HOLE # : DG05-294C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		141.23	143.92	MSED: Core is light to dark grey; Intense clay alteration and sericite alteration; Foliation difficult to see due to alteration; Foliation: At 141.23m = too altered; At 141.73m = 55-60° TCA; At 143.26m = 55-60° TCA.		2	2	4	1	
80		143.92	144.58	MSED: Dark grey siliceous MSED; Qtz veins between foliations; Foliation at 50-52° TCA.		1	1			
80		144.58	155.63	MSED: Grey to dark grey; Qtz veins between foliations; Foliations...At 144.58m = 50-55° TCA; At 146.3m = 55-60° TCA; At 147.83m = 65-70° TCA; At 149.35m = 60-65° TCA; At 150.88m = 55-60° TCA; At 152.4m = 50-55° TCA; At 153.92m = 45-50°; Phyllitic...At 147.61m = 23cm QZZ; Diss py on fracture faces.		2	2	2	1	
70	155.63 - 157.17	155.63	157.17	QZZ: Light grey in color; Low angle Cb veins are common; Core is highly fractured and broken.					2	
80	157.17 - 191.82	157.17	160.74	MSED: Dark grey phyllitic QZZ veins follow foliations; Cb veinlets present are fewer in number than previous; Foliation at 157.17 is 60-62° TCA; At 158.5m = 65-70° TCA; At 160.02 m = 65-70° TCA		2	2	2	1	
80		160.74	161.87	Siliceous MSED: Cb veinlets more common; Foliation at 55-62° TCA		2			2	
80		161.87	171.71	MSED: Dark grey to black; Carbonaceous Phyllitic; Qtz veins between foliations; Cb fills fractures in veins; Increase in Cb veins and veinlets which crosscut foliations; Foliations: @161.87m = 65-70° TCA; At 163.07m = 55-60° TCA; At 164.59m = 50-55° TCA; At 166.12m = 45-50° TCA; At 167.64m = 60-65° TCA; At 169.16m = 55-60° TCA; At 170.69m = 30-35° TCA: At 171.11m = 10cm fault gouge at 40° TCA, cut through 5cm qtz veins containing scorodite (1%); Foliation after fault 55-60° TCA		3	2	1	2	
80		171.71	171.87	MSED: 16cm qtz vein at 60° TCA; Grey quartz follows adjacent foliations; 1% po present; Trace aspy						
80		171.87	173.12	Siliceous MSED: Foliations difficult to see; Where visible, at 70° TCA, containing boudins					1	
80		173.12	174.76	Dark grey MSED: Contains boudins; Foliation at 47-50° TCA.		2	2	1	1	
80		174.76	177.18	Silicified MSED: Qtz veins larger (2-7cm) in this section; Foliation 55° TCA; Qtz veins have large selvages					1	
80		177.18	191.82	MSED: Light to dark grey color; Qtz veins follow foliation; Sulphide veinlets cross cut; Most sulphide veins/veinlets have been replaced by a soft, brown groundmass likely bt; Aspy tends to be altered to scorodite; Foliations: At 177.18m = 70° TCA; At 178.31m = 60-65° TCA; At 179.83m = 55-60° TCA; At 181.36m = 45-50° TCA; At 182.88m = 55-60° TCA; At 184.4m = 50-55° TCA; Carbonaceous and phyllitic		3	2	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 8 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B381052	137.16	138.68	<0.005			VA05064959	1.52
4	1	3.0	9.0	65							1.0											B381053	138.68	140.21	<0.005			VA05064959	1.53
1	1	3.0	3.0																			B381054	140.21	141.23	<0.005		Broken Pieces	VA05064959	1.02
0																						B381055	141.23	141.73	0.01			VA05064959	0.50
																						B381056	BLANK		<0.005			VA05064959	
2	1	0.2	0.4	60																		B381057	141.73	143.26	<0.005			VA05064959	1.53
2	1	0.2	0.4	60																		B381058	143.26	143.92	<0.005			VA05064959	0.66
6	1	0.2	1.2	50																		B381059	143.92	144.58	<0.005			VA05064959	0.66
3	1	0.2	0.6	50							0.1											B381060	144.58	146.30	<0.005			VA05064959	1.72
1	1	0.2	0.2	50																		B381061	146.30	147.83	<0.005			VA05064959	1.53
1	1	0.2	0.2	50																		B381062	146.30	147.83	<0.005	DUP		VA05064959	1.53
5	1	0.2	1.0	50																		B381063	147.83	149.35	<0.005			VA05064959	1.52
5	1	0.2	1.0	50																		B381064	149.35	150.88	<0.005			VA05064959	1.53
3	3	5.0	9.0	50																		B381065	150.88	152.40	<0.005			VA05064959	1.52
2	1	0.5	0.7	65																		B381066	152.40	153.92	<0.005			VA05064959	1.52
3	1	3.0	7.0	60							0.1											B381067	153.92	155.63	<0.005			VA05064959	1.71
5	6	0.1	0.5	30	60					30.0			20.0									B381068	155.63	157.17	0.03		Sulphide Veinlets	VA05064959	1.54
5	6	0.1	0.5	30	60					30.0			20.0									B381069	155.63	157.17	0.02	PD/CA		VA05064959	1.54
																						B381070	STANDARD 3C		0.09	3C		VA05064959	
2	1	3.0	5.0	60		3.0	chl	3	0	0.1												B381071	157.17	158.50	<0.005			VA05064959	1.33
5	1	3.0	8.0	60						0.1												B381072	158.50	160.02	<0.005			VA05064959	1.52
0																						B381073	160.02	160.74	<0.005			VA05064959	0.72
	4	0.1	30.0																			B381074	160.74	161.87	<0.005		Veinlets	VA05064959	1.13
3	1	0.2	0.6	75																		B381075	161.87	163.07	<0.005			VA05064959	1.20
																						B381076	BLANK		<0.005			VA05064959	
2	1	1.0	1.5	60																		B381077	163.07	164.59	<0.005			VA05064959	1.52
2	4	0.5	0.7	30																									
4	1	1.0	3.5	50																		B381078	164.59	166.12	<0.005			VA05064959	1.53
3	1	0.2	0.6	60																		B381079	166.12	167.64	<0.005			VA05064959	1.52
3	1	0.5	1.5	50																		B381080	167.64	169.16	0.02			VA05064959	1.52
0																						B381081	169.16	170.69	0.02			VA05064959	1.53
0																						B381082	169.16	170.69	0.01	DUP		VA05064959	1.53
1	1	5.0	5.0	40									0.1						90.0			B381083	170.69	171.71	<0.005			VA05064959	1.02
1	1	16.0	16.0	60							1.0		0.1					20.0				B381084	171.71	171.87	<0.005			VA05064959	0.16
																						B381085	171.87	173.12	<0.005			VA05064959	1.25
1		1.5	1.5	60									0.1						90.0			B381086	173.12	174.76	<0.005			VA05064959	1.64
6	1	6.0	12.0	50									5.0						90.0			B381087	174.76	175.26	0.09			VA05064959	0.50
4	1	2.0	5.5	55							3.0											B381088	175.26	176.78	0.01			VA05064959	1.52
4	1	2.0	5.5	55							3.0											B381089	175.26	176.78	0.01	PD/CA		VA05064959	1.52
																						B381090	STANDARD 2B		2.96	2B		VA05064959	
1	6	0.4	0.4	30																		B381091	176.78	177.18	<0.005		Sulphide replaced by fine grey-brown groundmass (biot?)	VA05064959	0.40
2	4	0.2	0.4	35																		B381092	177.18	178.31	<0.005		Crosscuts foliation	VA05064959	1.13
2	1	0.2	0.4	55																		B381093	178.31	179.83	<0.005			VA05064959	1.52
2	1	1.5	3.0	55																		B381094	179.83	181.36	0.01			VA05064959	1.53
2	6	0.2	0.4	135																									
4	1	0.2	0.8	55																		B381095	181.36	182.88	0.02			VA05064959	1.52

DRILL HOLE # : DG05-294C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70	191.82 - 198.60	191.82	198.60	QZZ: Light grey to brown; Foliation rarely visible; Very few veins (qtz and carb); Few Sulphide veinlets; Aspy altered to scorodite; Disseminated aspy found throughout -ox; Foliation at 55-60° where visible.					1	
80	198.60 - 234.70	198.60	202.34	MSED: Grey to dark grey; Phyllitic, Carbonaceous; Qtz Follows foliations, often irregular vein patterns; Foliations: At 198.6m = 60-65° TCA; At 199.64m = 65-70° TCA; At 201.17m = 45-60° TCA.		3	2	2	1	
80		202.34	205.54	Siliceous MSED: Light grey color; Increase in low angle cb veins; Foliations: At 202.34m = 52-55° TCA; At 204.22m = 65-70° TCA.					1	
80		205.54	209.79	MSED: Dark grey to black; Reduction in Carbonate veining; Qtz veins between foliation; Foliation: At 205.54m = 60-62° TCA; At 207.26m = 40-45° TCA crenulated; At 208.79m = 50-55° TCA boudins present; At 206.02m = 9cm grey quartz vein at 70° TCA; 1% py and 1% aspy.		2	1	2	1	
80		209.79	213.36	Siliceous MSED and QZZ; MSED grey, QZZ light grey; The QZZ has more veins, larger size and contains po (tr-1%) and disseminated po. Foliation: At 209.79m = 60-65° TCA; At 210.31m = Not visible; At 211.14m = 60-65° TCA; At 211.84m = 60-65° TCA; At 212.16m = Carb vein at 35° TCA; Contains 3% po; Carb veinlets also contain po.					1	
80		213.36	217.59	MSED: Grey to black; Very few veins present; Foliation: At 213.36m = 50-55° TCA; At 214.88m = 55-60° TCA; At 216.41m = 65-70° TCA; Boudins present after 215.52m.						
80		217.59	219.77	Siliceous MSED; Light grey color very little foliation visible; Foliation at 45-50°. At 217.59m a 40cm QZZ at 60° TCA.						
80		219.77	231.65	MSED: Dark grey to black; Phyllitic where dark grey, carbonaceous where black; Qtz veins crosscut foliation until 230.12m, where they run parallel. Foliation: At 220.98m = 60-65° TCA; At 222.5m = 55-60° TCA; At 224.03m = 55-60° TCA; At 225.55m - 50-55° TCA; At 227.08m = 45-50° TCA; At 228.60m = 55-60° TCA; At 230.12m = 60-62° TCA; At 220.11m = 2cm py vein at low angle 10-30° following contact with QZZ: The QZZ also has disseminated aspy, cpy; The contact between the two is a fault plane with 11-15cm of slip. Fault plane crosscut foliation; Slip was near vertical; Fault Zone is 40cm long at 25-30° TCA.		3	2	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B381096	BLANK		<0.005			VA05064959	
1	3	0.5	0.5	135						5.0												B381097	182.88	184.40	0.07		Crosscuts	VA05064959	1.52
2	1	0.5	1.0	60																		B381098	184.40	185.93	<0.005			VA05064959	1.53
5	1	2.0	4.0	50																		B381099	185.93	187.45	0.02			VA05064959	1.52
3	1	1.0	3.0	50																		B381100	187.45	188.98	<0.005			VA05064959	1.53
2	1	0.5	0.7	60																		B381101	188.98	190.50	<0.005			VA05064959	1.52
2	1	0.5	0.7	60																		B381102	188.98	190.50	<0.005	DUP		VA05064959	1.52
0																						B381103	190.50	191.82	<0.005			VA05064959	1.32
3	1	2.0	5.0	50						0.1								90.0				B381104	191.82	193.55	<0.005			VA05064959	1.73
	4	0.1		30																		B381105	193.55	195.07	<0.005		Veinlets	VA05064959	1.52
2	6	0.1	0.2	40						5.0								90.0				B381106	195.07	196.60	0.01			VA05064959	1.53
	4			60																		B381107	196.60	198.12	<0.005		Veinlets follow foliation	VA05064959	1.52
	4			60																		B381108	198.12	198.60	<0.005		Veinlets in between foliation	VA05064959	0.48
	4			60																		B381109	198.12	198.60	<0.005	PD/CA		VA05064959	0.48
																						B381110	STANDARD 5E		1.43	5E		VA05064959	
	4			60																		B381111	198.60	199.64	0.01		Veinlets	VA05066289	1.04
2	1	0.5	1.0	70																		B381112	199.64	201.17	<0.005			VA05066289	1.53
1	1	0.5	0.5	60																		B381113	201.17	202.34	0.01			VA05066289	1.17
	4			30																									
	4	0.1		40																		B381114	202.34	202.69	<0.005		Veinlets crosscut	VA05066289	0.35
5	1	4.0	7.0	60		0.1	q-k	3	0													B381115	202.69	204.22	<0.005			VA05066289	1.53
																						B381116	BLANK		<0.005			VA05066289	
2	6	0.1	0.2																			B381117	204.22	205.54	0.58		Sulphides replaced by brown fine grained mineral (biot?)	VA05066289	1.32
0																						B381118	205.54	206.02	<0.005			VA05066289	0.48
2	1	9.0	20.0	70						1.0			1.0									B381119	206.02	206.28	<0.005			VA05066289	0.26
	4			30																		B381120	206.28	207.26	<0.005		Veinlets, crosscut	VA05066289	0.98
0																						B381121	207.26	208.79	0.05			VA05066289	1.53
	4			30																		B381122	207.26	208.79	0.02	DUP	Veinlets Crosscut	VA05066289	1.53
	4			30																		B381123	208.79	209.79	<0.005			VA05066289	1.00
	4			30																		B381124	209.79	210.31	0.35			VA05066289	0.52
8	1	5.5	18.0	55						0.1			0.1									B381125	210.31	211.14	0.14			VA05066289	0.83
1	1	1.0	1.0	60																		B381126	211.14	211.84	0.01			VA05066289	0.70
1	4	0.2	0.2	145							3.0											B381127	211.84	213.36	0.18		Carb veinlets also contain po	VA05066289	1.52
1	1	1.0	1.0	60							1.0																		
	4	0.1		30	10																	B381128	213.36	214.88	<0.005		Veinlets crosscut	VA05066289	1.52
	4	0.1		30	10																	B381129	213.36	214.88	<0.005	PD/CA		VA05066289	1.52
																						B381130	STANDARD 4D		0.45	4D		VA05066289	
	4			60																		B381131	214.88	216.41	<0.005			VA05066289	1.53
	4			60																		B381132	216.41	217.59	<0.005			VA05066289	1.18
1	1	0.5	0.5	60																		B381133	217.59	219.19	0.01			VA05066289	1.60
2	1	3.0	6.0	60									0.1									B381134	219.19	219.77	0.05			VA05066289	0.58
0																						B381135	219.77	220.04	0.06			VA05066289	0.27
																						B381136	BLANK		<0.005			VA05066289	
2	6	2.0	2.2	10	20					60.0												B381137	220.04	220.62	0.18			VA05066289	0.58

DRILL LOG LEGEND P1

DRILL HOLE # : DG05-294C

DATE: July 16-28, 2005 PAGE 11 of 12

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		231.65	234.70	Siliceous MSED; Light grey; Carbonate alteration increased, as has veining; Foliation: At 231.65m = 60-62° TCA; At 233.17m = 60-62° TCA; 233.24m = 46cm fault zone at 25° TCA, py present along slip and in folded qtz veins; Veins suffered intense cb alteration; Slip plane crosscuts foliation; Similar to FZ above.		1		1	1	
81	234.70 - 237.00	234.70	237.00	HFLS MSED - Green-violet color; Qtz veins irregular, between residual foliations; Disseminated pyrite found throughout; Cb veining increased, common foliation at 55-60° TCA.		3	2		2	
70	237.00 - 240.60	237.00	240.60	QZZ: Light grey to grey-green; At 237.24m = 10cm mafic intrusive = Diabase Dyke at 60° TCA; Increase in qtz veining frequency and size.					1	
80	240.60 - 268.22	240.60	249.94	MSED: Dark grey (phyllitic) to black (carbonaceous); Reduction in number of Carbonate veinlets and alteration as well as qtz veins. Foliation: At 240.60m = 60-62° TCA; At 242.32m = 60-62° TCA; At 243.84m = 60-65° TCA; At 245.36m = 50-55° TCA; At 246.89m = 60-62° TCA; At 248.41m = 60-62° TCA; At 246.79m = 56cm of QZZ at 60° TCA.		3	1	1	1	
80		249.94	257.56	Siliceous MSED: Light grey to grey; Siliceous; Increase in number and size of quartz veins; Foliation is visible in several locations; Foliation: At 249.94m = 45-50° TCA; At 251.46m = 60-62° TCA; At 252.98m = 60-62° TCA; At 254.51m = 40-45° TCA; At 256.03m = 50-52° TCA; At 251.24m = Mineralized slip plane at 155° TCA; Crosscuts foliation, 1cm pyrite present, also disseminated pyrite; Slip direction consistent with other slip planes (near vertical).		1			2	
80		257.56	268.22	Siliceous MSED: Dark grey, foliation more visible; Less silicification than previous interval; Foliation: At 257.56m = 60-62° TCA; At 259.08m = 40-45° TCA; At 260.6m = 50-55° TCA; At 262.13m = 55-60° TCA; At 263.65m = 55-60° TCA; At 265.18m = 42-45° TCA; At 266.7m = 58-60° TCA. At 264.05m = 49cm carbonaceous, black phyllitic MSED, contact at 80° TCA; At 265.4m = 7cm qtz vn at 85° TCA (up hole), 30° TCA down hole.		1	1	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
1	3	2.0	2.0	30						30.0												B381138	220.62	221.08	0.04		Vein is pink	VA05066289	0.46
3	6	2.0	2.2	10	20					10.0			10.0									B381139	221.08	222.50	0.14			VA05066289	1.42
1	1	1.0	1.0	60																		B381140	222.50	224.03	0.02			VA05066289	1.53
1	4	0.2	0.2	45																		B381141	224.03	225.55	<0.005			VA05066289	1.52
1	4	0.2	0.2	45																		B381142	224.30	225.55	<0.005	DUP		VA05066289	1.25
1	2	0.2	0.4	60																		B381143	225.55	227.08	<0.005			VA05066289	1.53
2	3	3.0	6.0	60							3.0											B381144	227.08	228.60	0.01			VA05066289	1.52
	4			10																		B381145	228.60	230.12	<0.005		Veinlets, crosscut foliation	VA05066289	1.52
	4			10																		B381146	230.12	231.65	<0.005		Veinlets, crosscut foliation	VA05066289	1.53
1	1	3.0	3.0	50																		B381147	231.65	233.17	<0.005			VA05066289	1.52
1	3	3.0	3.0	56																		B381148	233.17	234.70	<0.005			VA05066289	1.53
1	3	3.0	3.0	56																		B381149	233.17	234.70	0.01	PD/CA		VA05066289	1.53
																						B381150	STANDARD 5E		1.43	5E		VA05066289	
1	1	3.0	3.0	50							1.0		1.0						90.0			B381151	234.70	236.22	<0.005			VA05066289	1.52
2	1	1.0	1.2	70									0.1						50.0			B381152	236.22	237.00	<0.005			VA05066289	0.78
7	1	4.0	9.0	55							0.1											B381153	237.00	237.74	<0.005			VA05066289	0.74
5	1	4.0	12.0	55							0.1		1.0						90.0			B381154	237.74	239.27	<0.005			VA05066289	1.53
3	1	1.0	1.4	65							0.1											B381155	239.27	240.60	<0.005			VA05066289	1.33
																						B381156	BLANK		<0.005			VA05066289	
	4			30																		B381157	240.60	241.13	<0.005		Cb veinlets	VA05066289	0.53
	4			30																		B381158	241.13	242.32	<0.005		Veinlets	VA05066289	1.19
	4			30																		B381159	242.32	243.84	<0.005		Veinlets	VA05066289	1.52
	4			30	10																	B381160	243.84	245.36	<0.005		Veinlets	VA05066289	1.52
2	1	0.2	0.4	50							0.1											B381161	245.36	246.89	<0.005			VA05066289	1.53
2	1	0.2	0.4	50							0.1											B381162	245.36	246.89	<0.005	DUP		VA05066289	1.53
1	1	0.5	0.5	55																		B381163	246.89	248.41	0.01			VA05066289	1.52
3	4	0.2	0.6	70						0.1												B381164	248.41	249.94	0.02			VA05066289	1.53
3	1	2.0	4.0	60						3.0												B381165	249.94	251.24	0.01			VA05066289	1.30
1	6	0.5	0.5	30						90.0												B381166	251.24	251.46	0.02			VA05066289	0.22
3	1	1.0	1.7	70																		B381167	251.46	252.98	<0.005			VA05066289	1.52
2	4	0.5	1.0	25																		B381168	252.98	254.51	<0.005			VA05066289	1.53
2	4	0.5	1.0	25																		B381169	252.98	254.51	0.01	PD/CA		VA05066289	1.53
																						B381170	STANDARD 3C		0.09	3C		VA05066289	
1	1	1.0	1.0	55																		B381171	254.51	256.03	<0.005			VA05066289	1.52
3	1	2.0	2.8	45																		B381172	256.03	257.56	<0.005			VA05066289	1.53
4	1	2.0	3.5	60							0.1	1.0							90.0			B381173	257.56	259.08	<0.005			VA05066289	1.52
3	1	1.5	4.0	40																		B381174	259.08	260.60	<0.005			VA05066289	1.52
5	1	4.0	9.0	55							3.0											B381175	260.60	262.13	<0.005			VA05066289	1.53
																						B381176	BLANK		<0.005			VA05066289	
2	4	0.2	0.4	30																		B381177	262.13	263.65	0.01			VA05066289	1.52
1	1	2.0	2.0	80									0.2									B381178	263.65	265.18	<0.005			VA05066289	1.53
1	1	6.0	6.0	80	30						1.0		0.1									B381179	265.18	266.70	<0.005			VA05066289	1.52
3	1	3.0	7.0	70									1.0						90.0			B381180	266.70	268.22	<0.005			VA05066289	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-295C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1022m

BEARING: 000 | DIP: -50°

DATE STARTED: 15-Jul-05 | DATE COMPLETED: 20-Jul-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459755 NORTHING: 7099152

COORD SYSTEM: NAD 83: EASTING: 459636 NORTHING: 7099337

NAD 27 (CORRECTED for historic grid): EASTING: 459725 NORTHING: 7099162

SECTION LINE(historic grid): 459725E

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden: 35.05m

Deviation:

Casing: 33.53m

Core Size: HQ & NQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
35.05	281.94	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B382387 to B382439

Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05

Lab Record #: VA05062471 Date Received: 17-Jul-05

Sample Sequence: B382440 to B382617

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Jul-05

Lab Record #: VA05064957 Date Received: 8-Aug-05

Duplicates:	B382402, B382422, B382442, B382462, B382482, B382502, B382522, B382542, B382562, B382582, B382602,
Preparation Duplicate/ Check Assay:	B382409, B382429, B382449, B382469, B382489, B382509, B382529, B382549, B382569, B382589, B382609,
Standards:	B382410(5E), B382430(6F), B382450(7G), B382470(2B), B382490(3C), B382510(4D), B382530(1A), B382550(5E), B382570(6F), B382590(7G), B382610(3C)
Blanks:	B382396, B382416, B382436, B382456, B382476, B382496, B382516, B382536, B382556, B382576, B382596, B382616

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	334.0	-53.3	000.0	001.0
180.0	334.9	-51.1	000.9	001.9
210.0	336.2	-48.6	002.2	003.2
281.9	338.2	-46.0	004.2	005.2

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Switched from HQ to NQ at 66.63m.

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 1 of 14			
DRILL HOLE # : **DG05-295C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 33.53	0.00	33.53	no recovery						
10	33.53 - 281.94	33.53	48.50	GND: v. broken up to crumbly GND. Limonite covers fracture faces and is pervasive through ~50% of rock. 14cm clay-gravel seam at 42.60m. Recovery is v. poor (ave ~40%).	3	0	0	1	2	
10		48.50	59.44	GND: Sand to gravel texture over 90% of section. Med yellowish brown. From 57.01 to 59.44m, rock is ox'd pervasively to sand/clay texture. Variable colours w/in, due to some hematite staining to deep reddish brown, and ox'd calcite to yellow. Overall colour med to light brown. One vein visible at 59.32m, in competent section 12cm wide. No selvage visible. Recovery is poor: 40%.	5	0	0	2	3	
10		59.44	64.01	GND still highly ox'd and ~40% alt'd such that GND texture is no longer visible; from competent (80%) to clay rich (20%). Recovery improved - up to 100% (lowest: 89%).	3	1		2	2	
10		64.01	79.38	GND: At 66.63m, core size switches from HQ to NQ. GND texture preserved in competent core with excellent recovery. Limonite throughout, in veinlets and in GND matrix. (Limonite contains carbonate.)	3				2	
10		79.38	89.92	GND: Unalt'd GND separated by wide chl/cb selvages around qtz veins, carb veins and sulph veins. V minor limonite staining in patches throughout rock	1	1	2		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: Drilled July 15-20, 2006

LOGGED BY: M. Stone

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.6	1.8	50		2.0	q	3	3	2.0								5.0				B382387	33.53	35.05	0.046			VA05062471	1.52
5	1	1.0	3.5	45	30	2.0	q/cb	2	4	5.0	5.0		20.0					1.0				B382388	35.05	36.58	0.084			VA05062471	1.53
5	1	1.0	3.5	45	30	2.0	q/cb	2	4	5.0	5.0		20.0					1.0				B382389	35.05	36.58	0.109	PD/CA		VA05062471	1.53
																						B382390	STANDARD 1A		0.764	1A		VA05062471	
0																						B382391	36.58	38.10	0.094			VA05062471	1.52
1	1	0.5	0.5	45		1.0	q/cb	1	3				15.0						2.0			B382392	38.10	39.62	0.025			VA05062471	1.52
0																						B382393	39.62	41.15	0.042			VA05062471	1.53
0																						B382394	41.15	42.67	0.102			VA05062471	1.52
1	1	1.0	1.0	30		1.5	q	1	3				5.0									B382395	42.67	44.20	0.036			VA05062471	1.53
																						B382396	BLANK		<0.005			VA05062471	
																						B382397	44.20	45.72	0.044			VA05062471	1.52
2	1	0.5	1.0	65		10.0	q	3	4	2.0									5.0			B382398	45.72	47.24	0.272			VA05062471	1.52
0																						B382399	47.24	48.50	0.044			VA05062471	1.26
0																						B382400	48.50	48.77	0.156			VA05062471	0.27
2	1	0.5	1.0	60		2.0	q/cb	4,3	3	8.0								5.0				B382401	48.77	50.29	0.029			VA05062471	1.52
2	1	0.5	1.0	60		2.0	q/cb	4,3	3	8.0								5.0				B382402	48.77	50.29	0.025	DUP		VA05062471	1.52
																						B382403	50.29	51.82	0.161			VA05062471	1.53
																						B382404	51.82	53.34	0.125			VA05062471	1.52
																						B382405	53.34	54.86	0.086			VA05062471	1.52
																						B382406	54.86	56.39	0.023			VA05062471	1.53
																						B382407	56.39	57.91	0.159			VA05062471	1.52
1	1	1.0	1.0							2.0								5.0				B382408	57.91	59.44	0.165		section all alt'd	VA05062471	1.53
1	1	1.0	1.0							2.0												B382409	57.91	59.44	0.149	PD/CA		VA05062471	1.53
																						B382410	STANDARD 5E		1.38	5E		VA05062471	
5	1	1.0	2.5	40	20					2.0	8.0							4.0				B382411	59.44	60.96	0.22			VA05062471	1.52
3	1	1.0	3.0	20		1.0	q/cb	3	4	12.0								4.0				B382412	60.96	62.48	0.159			VA05062471	1.52
1	1	1.0	1.0	40		5.0	q	2	3	0.1								4.0				B382413	62.48	64.01	0.076			VA05062471	1.53
1	4	1.0	1.0	45		20.0	cb	3	3																				
5	1	1.5	5.0	40	15	2.0	q/cb	2	3	20.0								5.0				B382414	64.01	65.53	0.075			VA05062471	1.52
2	1	3.2	4.0	15	60	1.0	q	2	3	3.0								5.0				B382415	65.53	66.63	0.057			VA05062471	1.10
																						B382416	BLANK		<0.005			VA05062471	
3	1	0.5	1.5	50		3.0	q/cb	2	3	5.0								5.0				B382417	66.63	67.89	0.329			VA05062471	1.26
2	3	0.4	0.4	135		1.0	q/cb	3	3	15.0								4.0				B382418	67.89	68.58	0.302			VA05062471	0.69
9	3	0.8	3.0	50	30	1.0	q/cb	3	2	4.0			1.0					4.0				B382419	68.58	69.66	0.053			VA05062471	1.08
1	1	1.0	1.0	20		1.0	q	4	1	2.0								5.0				B382420	69.66	70.66	0.077			VA05062471	1.00
1	6	0.4	0.4	35		2.0	q/cb	3	2	30.0			60.0					3.0											
1	6	0.4	0.4	45		1.5	q/cb	2	1	20.0			40.0					3.0				B382421	70.66	71.63	0.032			VA05062471	0.97
1	1	1.4	1.4	50		2.0	q/cb	3	3	2.0								4.0											
1	1	1.4	1.4	50		2.0	q/cb	3	3	2.0												B382422	70.66	71.63	0.056	DUP		VA05062471	0.97
4	1	12.0	15.0	50	30	1.0	q	2	2	7.0								5.0				B382423	71.63	73.22	0.086			VA05062471	1.59
3	3	0.3	0.9	35	80	4.0	q/cb/chl	3	1	0.1								5.0				B382424	73.22	74.68	0.08			VA05062471	1.46
1	1	1.3	1.3	20		0.5	q/cb	2	2	2.0			0.1					5.0											
7	1	1.0	7.0	40	60	2.0	q	2	3	5.0								5.0				B382425	74.68	76.21	0.043			VA05062471	1.53
5	1	1.0	5.0	20	40	2.0	q/chl	2	2	1.0	1.0		10.0					5.0				B382426	76.21	77.72	0.047			VA05062471	1.51
1	4	0.3	0.3	40		10.0	q/chl	4	2	20.0								5.0											
4	4	0.2	0.8	45	10	1.0	chl/cb	3	1	3.0								5.0				B382427	77.72	78.20	0.02			VA05062471	0.48
4	1	1.0	4.0	35		2.0	q/chl	2	1	5.0			10.0					5.0				B382428	78.20	79.38	0.112			VA05062471	1.18
3	4	0.2	0.6	15	50	6.0	cb/chl	3	1																				
3	4	0.2	0.6	15	50	6.0	cb/chl	3	1													B382429	78.20	79.38	0.274	PD/CA		VA05062471	1.18
																						B382430	STANDARD 6F		NSS	6F		VA05062471	
6	1	2.0	5.0	45		20.0	cb/chl	4	1		5.0		10.0					1.0				B382431	79.38	80.77	0.156			VA05062471	1.39
3	1	0.7	1.4	45		1.0	cb/chl	4	1		5.0		10.0					1.0				B382432	80.77	82.29	0.098		carb/sulph/qtz vein	VA05062471	1.52
3	4	1.0	1.4	45	60	40.0	cb/s	3	1	50.0								5.0											
							q/chl	2																					
6	1	2.0	5.4	60	25	1.0	q	3	1	5.0								2.0				B382433	82.29	83.82	0.647			VA05062471	1.53
							cb/chl	1																					
5	1	3.0	6.5	40		2.0	cb/chl	3	1		2.0		5.0					1.0	1.0			B382434	83.82	85.34	0.046			VA05062471	1.52
							q	2																					
2	1	0.6	1.0	40	10	1.0	q	3	1		5.0		5.0									B382435	85.34	86.87	0.068			VA05062471	1.53

DRILL LOG LEGEND P1	DATE: July 15-20, 2005	PAGE 3 of 14	
DRILL HOLE # : DG05-295C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		89.92	99.06	GND: silicified, aphanitic rock. Appearance is uniform dark grey with low-to-high angle carb veinlets, only 1mm wide, with ~1cm selvages. Few well-defined qtz veins	1		2		2	
10		99.06	106.68	GND: Chloritized/ ser'd GND with preserved texture.	1	2	3	1	2	
10		111.25	114.30	GND: v. crumbly dark grey GND. Ave cobble size is ~4cm in diameter. 2.5cm, pure qtz pebbles, two qtz veins in situ.			2	1	1	
10		114.30	126.49	GND: unalt'd GND separated by wide chlorite and carbonate-rich selvages. Sample actually only contains ~10-15% unalt'd GND due to the large amount of veins, and their large selvages (>30cm). Selvage at 115.50m hits unalt'd GND at 30° to CA (attributed to carb-qtz veins); veins are qtz, qtz-carb, and sulphide. Veins are called qtz-carb ("3") if carb content is greater than qtz content. Similarly, 'sulphide' veins ("6") contain more sulphides than anything else.		2	3	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

PAGE 4 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3	1.0	2.0	30		1.0	q/cb	4	1	10.0								5.0											
1	4	0.4	0.4	35		6.0	q/cb	4	2	1.0			3.0					5.0											
																						B382436	BLANK		<0.005			VA05062471	
5	4	0.3	1.0	25	120	1.0	q/cb	3			10.0		5.0					1.0				B382437	86.87	88.40	0.008			VA05062471	1.53
3	1	0.5	1.5	15	30					10.0			7.0					2.0	1.0			B382438	88.40	89.92	0.052		qtz incorp. into selvage of carb/sulph veins	VA05062471	1.52
3	4	0.6	1.0	35	80	30.0	q/chl	4	1	10.0								5.0											
3	3	1.0	1.4	45		1.0	cb/chl	4	1	20.0								5.0				B382439	89.92	91.45	0.029			VA05062471	1.53
1	4	0.2	0.2			2.0	cb	2														B382440	91.45	92.96	0.021		pieces (no angle)	VA05064957	1.51
1	1	0.5	0.5	10		2.0	q/chl	4		8.0								4.0				B382441	92.96	94.49	0.023			VA05064957	1.53
							cb	1																					
1	1	0.5	0.5	10		2.0	q/chl	4		8.0								4.0				B382442	92.96	94.49	0.022	DUP		VA05064957	1.53
1	1	1.0	1.0	30		2.0	q/chl	4		8.0	15.0							3.0				B382443	94.49	96.01	0.025			VA05064957	1.52
							cb	2																					
2	4	0.2	0.4	45	10	0.5	cb	3	1				4.0						1.0										
2	4	0.2	0.4	30	20	0.5	cb	3		0.1								4.0				B382444	96.01	97.54	0.005			VA05064957	1.53
3	1	1.0	2.5	25	50	4.0	chl/cb	4	1	5.0	5.0							4.0				B382445	97.54	99.06	0.2			VA05064957	1.52
							q	3																					
1	3	1.0	1.0	40		1.5	q/chl	3			15.0							1.0				B382446	99.06	100.58	0.039			VA05064957	1.52
							cb	3																					
3	1	1.2	2.7	15	5	2.0	q/chl	4	1	10.0			15.0	5.0								B382447	100.58	102.11	0.796			VA05064957	1.53
							cb	2																					
4	1	0.5	2.0	20	45	4.0	q/chl	3		5.0			10.0									B382448	102.11	103.64	6.44			VA05064957	1.53
4	1	0.5	2.0	20	45	4.0	q/chl	3		5.0			10.0									B382449	102.11	103.64	7.86	PD/CA		VA05064957	1.53
																						B382450	STANDARD 7G		4.35	7G		VA05064957	-
2	3	1.0	1.4	45	20	3.0	cb/chl	3					10.0						3.0			B382451	103.64	105.16	0.109			VA05064957	1.52
							q	2																					
4	1	1.0	3.5	45		1.0	q/chl/cb	2	1	3.0	8.0		0.1					1.0	3.0			B382452	105.16	106.68	0.105			VA05064957	1.52
3	3	0.5	1.5	30		1.0	cb	2					2.0																
4	1	1.0	2.5	40		2.0	q/chl/cb	3														B382453	106.68	108.20	0.016			VA05064957	1.52
1	3	5.0	5.0			1.0	cb	3			10.0							1.0											
2	3	2.0	3.0	35		3.0	chl/cb	3	1		5.0		3.0					1.0	2.0			B382454	108.20	109.73	0.013			VA05064957	1.53
							q	1																					
2	1	1.0	2.0	25		1.5	q	4					1.0						4.0			B382455	109.73	111.25	0.014			VA05064957	1.52
2	3	0.3	0.6	15	50	4.0	q/ch	3		10.0	10.0							2.0											
							cb	2																					
																						B382456	BLANK		<0.005			VA05064957	
5	1	2.5	8.0	50						2.0			3.0					5.0				B382457	111.25	112.77	0.089		most qtz in pieces	VA05064957	1.52
1	1	0.5	0.5	40							3.0											B382458	112.77	114.30	0.159			VA05064957	1.53
1	4	0.2	0.2	145																									
1	1	0.4	0.4	50		65.0	cb/chl	4	1	0.1								5.0				B382459	114.30	115.83	0.021		selvage for all veins	VA05064957	1.53
							q/s	2																					
2	3	0.5	1.0	30						5.0								5.0											
7	1	1.3	7.0	35	45	20.0	cb/chl	3			8.0											B382460	115.83	117.35	0.193			VA05064957	1.52
							q/s	2																					
2	3	0.2	0.4	140		1.0	cb	2		0.1								5.0											
7	1	1.2	6.0	30	40	4.0	chl/cb	4			10.0											B382461	117.35	118.87	0.07			VA05064957	1.52
							q/s	1																					
7	1	1.2	6.0	30	40	4.0	chl/cb	4			10.0											B382462	117.35	118.87	0.139	DUP		VA05064957	1.52
4	4	0.2	0.8	150		1.0	cb	2		0.1								5.0											
5	1	1.0	4.0	40	10	150.0	cb/chl	3		15.0	8.0		2.0				0.1					B382463	118.87	120.40	0.064		selvage for both vein types	VA05064957	1.53
							q/s	3,1																					
5	3	1.5	3.5	110	60					20.0								2.0											
8	1	1.0	6.0	30	40	25.0	cb/chl	3	1	10.0	5.0	1.0						5.0				B382464	120.40	121.92	0.175		ox'n of carb	VA05064957	1.52
							q/s	2																					
1	6	1.0	1.0	50		14.0	q/chl/cb	3		90.0			10.0					5.0											
3	4	1.0	2.0	20	60	6.0	cb/chl	4	1																				
							q/s	1																					
3	3	1.0	3.0	40	30	10.0	cb/q	3					10.0						2.0			B382465	121.92	123.44	0.035		from clay to competent carb	VA05064957	1.52
2	1	1.0	2.0	30		30.0	cb/chl	4		3.0	5.0		5.0					3.0											
							q/s	2																					

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 5 of 14	
DRILL HOLE # : DG05-295C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd. Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		126.49	132.99	GND: First metre is gradation into aphanitic, pale greenish grey to dark grey, uniform texture, except veinlets of carbonate at 20° and 140° to CA (approx 40 per metre). Weak slickensides on fracture faces. Carb-qtz veins appear 'smeared' out, with both qtz and carb in elongate, thin lenses.	1	1	3	2	2	
10		132.99	140.21	GND: unalt'd GND separated by chl'd and carb'd selvages, not as wide as before, up to 20cm in width. Section is ~60% unalt'd GND, and 40% alt'd; all is solid and competent with v good recovery. Qtz veins have much smaller, silicified selvages while carb veins have larger carb'd and chl'd selvages.		1	2		2	
10		140.21	141.73	GND: One sample with intense chl and carb alt'n. Sulphides in veinlets accumulated in zone from 140.75 to 141.05m, with carbonate in clear, large veins. Within selvage, carbonate forms 1-4mm grains with irregular shape but stand out amongst chl'd GND.			4	1	3	
10		141.73	152.41	GND: A lot less carb here. Unalt'd GND with qtz veins. Carb-qtz veins contain more and larger po and aspy than qtz veins. At 146.10 to 146.30m, fracture face at 5° to CA shows strong slickensides in chl and qtz and calcite to 50°.		1	1		1	
10		152.41	155.49	GND: Dark grey, aphanitic, silicified GND. Only 1mm bt preserved. Carb'd, chl'd selvages surround qtz/carb/sulph veins (up to 2cm), and veinlets (up to 1cm). One vein of unalt'd GND intrudes this aphanitic silicified rock. 2.4cm wide, at 15° to CA, at 154.30m.	1	1	2		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

PAGE 6 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
5	4	1.0	2.3	20	30	10.0	cb/chl	4		0.1								5.0				B382466	123.44	124.97	**1.215**			VA05064957	1.53
2	3	0.5	1.0	50		10.0	q/cb	3		20.0								1.0											
							chl/s	3																					
5	1	1.0	5.0	40		6.0	cb/chl	4					0.1						1.0			B382467	124.97	126.49	**0.075**			VA05064957	1.52
							q	1																					
3	3	18.0	20.0	50		10.0	q/chl/cb	4		5.0			3.0					1.0											
2	4	0.5	1.0	70	20	4.0	cb	3														B382468	126.49	128.01	**0.464**			VA05064957	1.52
2	3	8.0	9.0	50	70	10.0	q/cb	3		15.0	3.0							4.0											
3	1	1.0	3.0	55	50	2.0	q/chl	4		10.0	5.0		5.0					2.0	2.0										
3	1	1.0	3.0	55	50	2.0	q/chl	4		10.0	5.0		5.0					2.0	2.0			B382469	126.49	128.01	**0.429**	PD/CA		VA05064957	1.52
																						B382470	STANDARD 2B		**3.42**	2B		VA05064957	
9	3	0.3	1.5	40	70	1.0	q/cb	1		2.0								5.0				B382471	128.01	129.54	**0.233**		veinlets btwn 40° and 70°	VA05064957	1.53
2	6	0.3	0.5	85		1.0	q	3		100.0								5.0											
2	1	1.0	2.0	45		1.0	q/cb	3		0.1								5.0				B382472	129.54	131.07	**0.105**			VA05064957	1.53
2	3	1.0	2.0	60		2.0	cb	2		1.0								5.0											
1	6	0.4	0.4	30		2.0	cb/chl	3	1	100.0								5.0											
0																						B382473	131.07	132.59	**0.583**		~40 carb veinlets (random orientations)	VA05064957	1.52
3	1	0.8	2.4	40		8.0	q/chl	4		2.0	12.0							5.0				B382474	132.59	132.99	**0.342**		ox'd py, not po	VA05064957	0.40
							cb	1																			carb veinlets continue (<1mm), 80-90° to CA		
3	3	0.2	0.5	40	120	2.0	cb/chl	4					2.0									B382475	132.99	134.32	**0.062**			VA05064957	1.33
1	1	1.0	1.0	15		1.0	q	2		1.0	8.0		4.0						4.0										
																						B382476	BLANK		**0.006**			VA05064957	
9	1	0.6	3.0	40	25	1.0	q/chl	3,2														B382477	134.32	135.64	**0.083**		late carb veinlets through	VA05064957	1.32
							cb	1			15.0							1.0											
3	1	0.5	1.5	30		3.0	q/chl	3	1		12.0		0.1					1.0				B382478	135.64	136.39	**0.097**			VA05064957	0.75
							cb	3																					
5	1	1.3	4.5	30	50	3.0	q/chl	5	1		12.0		6.0					1.0				B382479	136.39	137.15	**0.032**			VA05064957	0.76
1	4	0.2	0.2	85		8.0	cb	4																					
5	1	1.0	3.9	35	15	2.0	q/chl	4			15.0		2.0									B382480	137.15	137.90	**0.054**		copper-coloured po	VA05064957	0.75
4	1	1.0	3.0			2.0	q/chl	4														B382481	137.90	138.68	**0.148**			VA05064957	0.78
2	4	0.4	0.8			20.0	cb	3																					
2	4	0.4	0.8			20.0	cb	3														B382482	137.90	138.68	**0.048**	DUP		VA05064957	0.78
5	1	1.2	3.2	40	50	3.0	q/chl/cb	4			8.0	4.0	4.0									B382483	138.68	139.58	**0.202**			VA05064957	0.90
4	4	0.2	0.8	60	70	10.0	cb	4														B382484	139.58	140.21	**0.356**			VA05064957	0.63
4	6	3.0	6.0	35		100.0	cb/chl	4		100.0								4.0				B382485	140.21	141.73	**0.127**			VA05064957	1.52
2	4	2.0	3.5	40																									
3	1	1.1	3.0	35		2.0	q/cb	2					4.0																
7	1	1.0	5.0	30	60	2.0	q/cb	3		3.0	5.0		6.0						2.0			B382486	141.73	143.26	**0.015**			VA05064957	1.53
2	1	0.6	1.8	35		2.0	q/chl	3		1.0			3.0									B382487	143.26	144.78	**0.04**			VA05064957	1.52
4	3	2.0	5.0	40	30	10.0	cb/s	3	1	2.0	20.0		2.0																
2	1	0.5	1.0	30	35	1.0	q	3			3.0		2.0									B382488	144.78	146.30	**0.034**			VA05064957	1.52
1	3	0.7	0.7	40		0.5	q/cb	3			10.0		2.0						2.0										
1	3	0.7	0.7	40		0.5	q/cb	3			10.0		2.0						2.0			B382489	144.78	146.30	**0.021**	PD/CA		VA05064957	1.52
																						B382490	STANDARD 3C		**0.094**	3C		VA05064957	
6	1	1.0	3.0	35	40	1.0	q	3			15.0											B382491	146.30	147.83	**0.172**			VA05064957	1.53
3	1	0.6	2.4	50		0.5	q	3			5.0		15.0						4.0			B382492	147.83	149.38	**0.025**			VA05064957	1.55
2	3	0.5	1.0	40		1.5	cb/chl	4			4.0		10.0						3.0										
1	4	0.2	0.2	70																									
3	1	0.4	1.2	35		1.0	q/cb	2			20.0											B382493	149.38	150.88	**0.071**		6 carb veinlets at ~35° to CA	VA05064957	1.50
6	1	1.0	4.0	40		15.0	q/cb	4		10.0	5.0							5.0				B382494	150.88	152.41	**0.089**		carb increase in selvages	VA05064957	1.53
							chl	3																					
1	1	0.3	0.3	40		2.0	q/chl	4					0.1									B382495	152.41	153.92	**0.025**			VA05064957	1.51
							cb/chl	2																					
																						B382496	BLANK		**<0.005**			VA05064957	
1	GND	2.5	2.5	40																		B382497	153.92	154.62	**0.019**			VA05064957	0.70
1	1	0.3	0.3	45		2.0	q/chl	3					5.0																

DRILL LOG LEGEND P1	DATE: July 15-20, 2005	PAGE 7 of 14	
DRILL HOLE # : DG05-295C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		155.49	164.66	GND: Back to unalt'd GND w/ small qtz veins with po. Carb in selvages and a few veinlets		1	1		2	
10		164.59	177.90	GND: Section is 40% carbonate-rich competent GND. Selvages around carb/qtz/sulph veins and veinlets. GND texture preserved throughout. Sulphide veins in first sample - 164.59 to 166.12m indicate a sense of shear, dextral if vein is to 40°. Shear zone is 15cm wide, actual.		1	1		3	
10		177.90	182.62	GND: 90% alt'd with carb and chl but still competent with 100% recovery. Actual carbonate veins appear: approx 2 per metre and 0.5 to 2cm wide		2	4		3	
10		182.62	192.03	GND: 60% unalt'd GND. Carbonate veins and qtz veins w/ po continue, but fewer and smaller sulphide veins (explains less alt'n). One 4cm carb vein at 185.25m contains large, brecciated clasts of chl'd GND 1-4cm in diameter.	1		2		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	3	0.4	0.8	30		3.0	q/cb	3			20.0	0.1	10.0					1.0				B382498	154.62	155.49	**0.114**			VA05064957	0.87
4	1	1.0	2.2	40		1.0	q	3			5.0		5.0					4.0	3.0			B382499	155.49	156.97	**0.05**			VA05064957	1.48
5	1	1.0	4.0	40	15	10.0	q/cb	3	1		10.0		5.0						3.0			B382500	156.97	158.49	**0.032**		carb ox'n	VA05064957	1.52
3	1	1.0	3.0	40	30	4.0	q	4			7.0		3.0						3.0			B382501	158.49	160.02	**0.048**			VA05064957	1.53
3	1	1.0	3.0	40	30	4.0	q	4			7.0		3.0						3.0			B382502	158.49	160.02	**0.023**	DUP		VA05064957	1.53
2	1	1.0	1.5	40		2.0	q	4	1				5.0						1.0			B382503	160.02	161.56	**0.179**			VA05064957	1.54
5	3	1.2	3.8	35	50	2.0	q/cb	4			5.0		20.0																
3	1	1.0	2.0	15	40	2.0	q/chl	3			8.0		4.0						1.0			B382504	161.56	163.07	**0.108**			VA05064957	1.51
1	6	0.3	0.3	70		15.0	cb/chl	3,1		100.0								5.0											
4	3	0.5	1.8	35		2.0	cb/chl	2			10.0		2.0					2.0	2.0										
6	1	1.4	5.6	50	25	8.0	cb/chl	4	1		6.0							3.0				B382505	163.07	164.59	**0.357**			VA05064957	1.52
1	6	0.8	0.8	60		4.0	cb	2	2	100.0								5.0											
5	6	0.4	1.4	30	40	20.0	cb/q	4		80.0	15.0				5.0			4.0				B382506	164.59	166.12	**0.086**			VA05064957	1.53
							chl	1																					
2	1	1.0	1.4	30		3.0	q/chl	4			5.0		5.0									B382507	166.12	167.69	**0.15**			VA05064957	1.57
3	3	1.5	3.2	40		4.0	q/cb	4			5.0		15.0					1.0	1.0										
							chl	2																					
5	1	1.5	3.5	35		20.0	cb/chl	4			10.0		5.0					3.0				B382508	167.69	169.16	**0.06**			VA05064957	1.47
							q	2																					
5	1	1.5	3.5	35		20.0	cb/chl	4			10.0		5.0					3.0				B382509	167.69	169.16	**0.064**	PD/CA		VA05064957	1.47
																						B382510	STANDARD 4D		**0.401**	4D		VA05064957	
3	3	0.3	0.9	40		4.0	q/cb	4		0.1								5.0				B382511	169.16	169.96	**0.052**			VA05064957	0.80
1	1	1.0	1.0	45		10.0	cb/chl	4			20.0		15.0						1.0										
2	1	0.6	1.2	45		2.0	q/cb	4			7.0		1.0					2.0	3.0			B382512	169.96	170.64	**0.522**			VA05064957	0.68
3	3	0.5	0.9	25	40	2.0	cb/chl	3		0.1								5.0											
5	1	1.0	5.0	30	50	6.0	cb/q	4			10.0		5.0						1.0			B382513	170.61	172.21	**0.272**			VA05064957	1.60
							chl	1																					
3	4	0.3	0.8	5	20	3.0	cb	3		0.1								5.0											
3	1	1.2	1.8	30		10.0	cb/q	4	1		15.0	1.0	8.0						3.0			B382514	172.21	173.74	**0.067**			VA05064957	1.53
							chl	1																					
2	3	0.4	0.7	45		2.0	cb/chl	3			10.0	1.0																	
3	1	9.0	11.0	70		25.0	cb/chl	5,4	1	15.0								3.0				B382515	173.74	175.26	**0.164**			VA05064957	1.52
																						B382516	BLANK		**<0.005**			VA05064957	
5	1	3.0	6.0	35	70	2.0	q	4														B382517	175.26	176.78	**0.096**		sulph w/ carb	VA05064957	1.52
						10.0	cb/chl	3																			numerous carb veinlets w/ 1cm selvages		
2	6	0.7	1.4	25	80	8.0	cb/chl	4		5.0			3.0					2.0											
4	1	1.0	2.5	50		2.0	cb/chl	3			35.0											B382518	176.78	177.90	**0.072**			VA05064957	1.12
							q	3																					
1	3	0.2	0.2	10		3.0	chl/cb	3		5.0			3.0					2.0											
4	1	1.0	4.0	60	70	10.0	cb/chl	5														B382519	177.90	178.31	**0.056**		one w/ carb	VA05064957	0.41
3	6	0.4				1.0				100.0								2.0											
3	4	0.6	1.5	30		40.0	chl/cb	5		10.0		2.0						5.0				B382520	178.31	179.84	**0.08**			VA05064957	1.53
5	1	1.5	6.5	45		5.0	q/cb	4			15.0		10.0						4.0										
							chl	2																					
4	4	1.5	2.8	30	45	20.0	q/cb/chl	5		10.0								4.0				B382521	179.84	181.36	**0.107**			VA05064957	1.52
5	1	1.0	3.5	35	60	6.0	q/chl/cb	4			6.0		4.0						3.0										
5	1	1.0	3.5	35	60	6.0	q/chl/cb	4			6.0		4.0						3.0			B382522	179.84	181.36	**0.098**	DUP		VA05064957	1.52
5	4	0.8	2.5	40	70	20.0	cb/chl	5		5.0			3.0					2.0				B382523	181.36	182.63	**0.134**			VA05064957	1.27
4	1	1.2	4.0	40		6.0	q/cb/chl	4			10.0																		
3	1	1.0	2.0	60	40	2.0	q/cb/chl	3			5.0		10.0					1.0	3.0			B382524	182.62	183.44	**0.044**			VA05064957	0.82
5	1	3.0	7.5	40		3.0	q/chl	3			5.0		15.0						4.0			B382525	183.44	184.18	**0.034**			VA05064957	0.74
7	1	3.0	8.0	55	85	15.0	cb/chl	4	1		10.0				3.0							B382526	184.18	185.42	**0.05**		carb vein w/ brecciated GND	VA05064957	1.24
2	4	4.0	5.0	60	80	8.0	q/chl	5	1	5.0								5.0											
							cb	2																					
																						B382527	185.42	186.44	**0.034**			VA05064957	1.02
4	4	0.5	2.0	70		20.0	cb/chl	5		0.1								5.0				B382528	186.44	187.45	**0.268**			VA05064957	1.01
5	1	1.0	3.5	40	60	10.0	q/cb	4			15.0		3.0						5.0										
							chl	2																					
4	4	0.5	2.0	70		20.0	cb/chl	5		0.1								5.0				B382529	186.44	187.45	**0.146**	PD/CA		VA05064957	1.01
5	1	1.0	3.5	40	60	10.0	q/cb	4			15.0		3.0						5.0										
																						B382530	STANDARD 1A		**0.875**	1A		VA05064957	

DRILL LOG LEGEND P1	DATE: July 16-20, 2005	PAGE 9 of 14	
DRILL HOLE # : DG05-295C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		192.03	196.70	GND: Zone of extreme alt'n; all silicified and chloritized, and carbonate-rich. Sulphide veins and veinlets reappear. Last sample (195.61-196.7m), contains many (7) sulphide veins, all but one are >90% ox'd py. One vein is unox'd. Massive aspy here as well, not in straight vein, but more irregular.	1	1	4		3	
10		196.70	207.27	GND: Unalt'd GND with far fewer veins			1		1	
10		207.27	220.98	GND: Increase in carbonate within GND causes rock to be crumbly and v broken up. Longest core is ~30cm, but only 2 lengths. Low-angle carbonate and qtz veins still visible in angular fragments; veins have corroded edges, so are silicifying GND - not sharp boundaries, difficult to spot (most). One qtz vein at 211.30m is 2.5cm and has ~20% sulphides: po and py. No selvage. On the surface of this vein a strong lineation appears in calcite, bt and clay-alt'd feldspars. Sample from 220.98 to 222.51m contains sulphide-rich qtz veins. At 60°, vein contains 30% massive aspy. Vein at 50° contains 15% po and 5% cpy (no aspy)		1	1	1	2	
10		220.98	224.03	GND: One sample. Chloritized section surrounding sulph-rich qtz veins and sulphide veinlets (ox'd py). Small clay alt'n due to carb.	1	1	3	1	2	
10		224.03	234.69	GND: Unalt'd, somewhat finer-grained GND. Ave mineral size is 1-2mm. Many episodes of sheeted qtz veins; some are difficult to see, others are clear, all are at similar angle (50-60°)			1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

PAGE 10 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
6	1	1.5	4.5	25	50	10.0	q/cb	4			15.0		10.0						1.0			B382531	187.45	188.46	0.06			VA05064957	1.01
							chl	2																					
1	4	0.3	0.3	145																									
4	1	2.0	6.0	30	45	8.0	cb/q/chl	4		3.0	5.0		15.0									B382532	188.46	189.48	0.087			VA05064957	1.02
3	3	1.0	1.8	60		10.0	q/cb/chl	4		2.0								5.0				B382533	189.48	190.50	0.174			VA05064957	1.02
3	1	2.0	3.5	60	45	4.0	q/cb	3			15.0		5.0																
5	1	1.0	5.0	60		8.0	q/cb/chl	4		5.0	3.0		5.0					5.0				B382534	190.50	192.03	0.1		selvage may not be due to vein; vein may be later	VA05064957	1.53
3	1	1.5	4.0	55	25	18.0	q/cb/chl	4	1	10.0	20.0		10.0					3.0				B382535	192.03	193.55	0.13			VA05064957	1.52
3	4	1.2	2.8	60		20.0	q	4		3.0								5.0											
																						B382536	BLANK		<0.005			VA05064957	
7	1	2.0	7.5	60	50	12.0	q/cb	4	1	3.0	10.0		5.0									B382537	193.55	194.60	0.325			VA05064957	1.05
5	6	0.5	2.5	60	70	30.0	cb/chl	5	1	100.0								4.0											
5	1	1.3	4.6	35	55	20.0	cb/chl	5		1.0	10.0		5.0									B382538	194.60	195.61	0.049			VA05064957	1.01
1	6	0.2	0.2	55		20.0	cb/chl	4		100.0								5.0											
4	1	1.0	3.0	40	80	6.0	q/cb/chl	4		10.0			10.0									B382539	195.61	196.70	0.392			VA05064957	1.09
7	6	1.0	5.0	60	50	40.0	q/cb/chl	5		90.0			10.0					4.0											
4	4	1.0	2.0	50						3.0								5.0											
4	1	3.0	5.5	60		2.0	q/chl	1		10.0	8.0		4.0					4.0				B382540	196.70	198.17	0.141			VA05064957	1.47
4	1	5.0	5.5	65		4.0	q/chl	3					5.0						2.0			B382541	198.17	199.64	0.064			VA05064957	1.47
2	3	0.5	1.0	60		2.0	q/cb	3			10.0		3.0																
2	3	0.5	1.0	60		2.0	q/cb	3			10.0		3.0									B382542	198.17	199.64	0.098	DUP	ox'n of hematite in selvage	VA05064957	1.47
5	3	2.0	6.5	60		2.0	q/cb	3		5.0			5.0					4.0	2.0			B382543	199.64	201.17	0.301			VA05064957	1.53
6	1	1.0	5.0	60	40	2.0	q	3		10.0	4.0		3.0					5.0				B382544	201.17	202.69	0.088			VA05064957	1.52
1	6	0.3	0.3	55		1.0	q/cb	2	2	100.0								5.0											
4	1	1.0	3.5	40		1.0	q	3			5.0		10.0						4.0			B382545	202.69	204.21	0.049			VA05064957	1.52
8	1	1.0	4.5	40	60	3.0	q/chl	3			10.0		8.0						2.0			B382546	204.21	205.74	0.043			VA05064957	1.53
8	1	1.0	6.5	45	70	5.0	q/chl	3			12.0		5.0						4.0			B382547	205.74	207.27	0.058			VA05064957	1.53
3	1	4.5	5.5	60		30.0	q/chl	5		7.0	15.0		5.0					4.0				B382548	207.27	208.79	0.343			VA05064957	1.52
3	1	4.5	5.5	60		30.0	q/chl	5		7.0	15.0		5.0					4.0				B382549	207.27	208.79	0.284	PD/CA	alt'd aspy	VA05064957	1.52
																						B382550	STANDARD 5E		1.49	5E	old' vein - has euhedral 1mm aspy	VA05064957	
2	1	1.0	1.8	30		4.0	q	3					5.0						5.0			B382551	208.79	210.32	0.075		new' vein	VA05064957	1.53
4	1	1.0	3.2	30	50	1.0	q	4					1.0									B382552	210.32	211.84	0.024			VA05064957	1.52
1	1	2.5	2.5	35						3.0	20.0							3.0											
3	3	0.6	1.8	50		1.0	q/cb	3			12.0											B382553	211.84	213.36	0.133			VA05064957	1.52
2	6	0.4	0.8	50	55	1.5	q	3			65.0		20.0					1.0											
3	1	1.0	2.0	40		4.0	q/cb	4			12.0											B382554	213.36	214.88	0.214		new vein	VA05064957	1.52
3	4	1.0	1.8	20		0.5	cb	3		0.1								5.0											
1	1	2.5	2.5	60		1.0	q/cb	2			5.0		2.0						1.0			B382555	214.88	216.40	0.042		old veins	VA05064957	1.52
							chl	2																					
2	1	0.5	1.0	60		2.0	q	2			5.0																	aspy in selvage; euhedral po and aspy		
																						B382556	BLANK		<0.005			VA05064957	
5	1	1.0	5.0	30	60	1.5	q/cb	4					2.0									B382557	216.40	217.93	0.035			VA05064957	1.53
1	6	0.5	0.5	40		4.0	q	4		15.0	65.0		5.0					4.0											
4	1	1.0	2.5	60		1.0	q/cb	3			8.0		5.0									B382558	217.93	218.68	0.977		one sulph ox'd, one not	VA05064957	0.75
3	1	2.0	4.0	60		4.0	q	4			20.0							1.0				B382559	218.68	219.46	0.226			VA05064957	0.78
4	1	0.5	2.0	65		2.0	q	4			30.0											B382560	219.46	220.26	0.675		aspy in selvages	VA05064957	0.80
2	6	0.5	1.0	65		35.0	cb/chl	4		100.0								2.0											
4	1	1.0	4.0	40		5.0	q/chl	3			5.0		6.0									B382561	220.26	220.98	1.35		aspy and po in different veins	VA05064957	0.72
4	1	1.0	4.0	40		5.0	q/chl	3			5.0		6.0									B382562	220.26	220.98	1.18	DUP	ox'd py at margins of qtz veins	VA05064957	0.72
6	1	2.0	8.5	60		2.0	q/chl	3			15.0	5.0	30.0									B382563	220.98	222.51	0.247			VA05064957	1.53
4	1	2.0	5.5	60		20.0	q/chl	2		15.0								3.0				B382564	222.51	224.03	0.093			VA05064957	1.52
2	6	0.3	0.5	50		40.0	chl/cb	4,2		100.0								4.0											
6	1	1.0	5.5	50	60	1.0	q/cb	3			10.0	1.0										B382565	224.03	225.55	0.176			VA05064957	1.52
							chl	1																					
1	4	0.4	0.4	25						1.0								5.0											

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 11 of 14	
DRILL HOLE # : DG05-295C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		234.69	236.22	GND: Concentration of sulphide veinlets (ox'd py) within carbonate-rich, crumbly GND	2		1	1	4	
10		236.22	245.36	GND: Highly alt'd section - carb-infused and chloritized. Sulphide vein(let)s continue, approx 4 per metre. Sample from 239.09 to 239.39m is one 21cm qtz vein with only one preserved selvage (upper). Lenses of sulphide within are up to 1cm wide. Diamagnetism of these lenses indicates presence of bismuthinite (but not visible).	3	1	2	1	3	
10		245.36	251.46	GND: Fine-grained unalt'd GND w/ minor sheeted qtz veins and minor carb alt'n.					1	
10		251.46	254.51	GND: Carbonate appears in veins; result is minor carb alt'n over 50% of section. One carbonate vein (1.3cm wide) at 252.95m has 24cm chl'd/carb'd selvage but sulphides are not prominent in carb'd section. More po (nice, large grains), in qtz veins with irregular edges.	1	1	1	1	1	
10		254.51	260.60	GND: Coarse GND texture preserved over 30% of section. Wide chloritic and oxidized selvages around qtz veins. Rare euhedral 2mm aspy disseminated in these selvages. Massive pyrite veins (only partly ox'd) at 258.70m.	2	1	2		2	
10		260.60	263.65	GND: Highly alt'd around qtz/carb/sulph veins.	1	1	3		2	
10		263.65	266.70	GND: V minor chloritic and carbonitic alt'n around qtz/carb/sulph veins.	1		1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.5	4.5	60	40	2.0	q/chl	2,1			5.0											B382566	225.55	227.08	0.097			VA05064957	1.53
6	1	1.0	4.0	30		0.5	q/cb	2			5.0		4.0					3.0				B382567	227.08	228.61	0.204			VA05064957	1.53
2	6	1.0	1.5	30		20.0	cb/chl	4,2		100.0								5.0											
3	1	3.0	5.0	35		16.0	q/cb	3			5.0							1.0				B382568	228.61	230.12	0.659			VA05064957	1.51
3	1	3.0	5.0	35		16.0	q/cb	3			5.0							1.0				B382569	228.61	230.12	0.546	PD/CA		VA05064957	1.51
																						B382570	STANDARD 6F		2.86	6F		VA05064957	
6	1	1.5	4.5	60	40	1.0	q	2			5.0		3.0									B382571	230.12	231.65	0.093			VA05064957	1.53
4	1	2.0	6.0	30		1.0	q/chl	1			10.0		1.0					1.0				B382572	231.65	233.17	0.223			VA05064957	1.52
6	1	1.0	4.5	35	70	1.0	q/cb	1		5.0	8.0							5.0				B382573	233.17	234.69	0.772			VA05064957	1.52
15	6	0.8	13.0	70		75.0	cb	4	1	100.0								5.0				B382574	234.69	235.44	4.4			VA05064957	0.75
12	6	0.4	4.5	60		78.0	cb	4	1	100.0								5.0				B382575	235.44	236.22	2.02			VA05064957	0.78
							chl	1																					
																						B382576	BLANK		<0.005			VA05064957	
2	3	1.5	3.0	70		2.0	q/cb	1			5.0											B382577	236.22	237.70	0.061			VA05064957	1.48
2	4	1.0	1.5	60		10.0	cb/chl	2		0.1								5.0											
4	1	1.0	4.0	40		2.0	q/cb	3		5.0			0.1					5.0				B382578	237.70	239.09	0.332			VA05064957	1.39
1	1	21.0	21.0	40		20.0	cb/chl	5		10.0	8.0		5.0	0.1								B382579	239.09	239.39	3.6			VA05064957	0.30
20	6	0.4	5.0	70		30.0	cb	4		100.0								5.0				B382580	239.39	240.89	0.161			VA05064957	1.50
2	3	1.0	2.0	70	2	2.0	cb/chl	4		10.0								5.0											
2	3	0.3	0.6	30		1.0	cb	3		2.0			4.0					5.0				B382581	240.89	242.32	0.134			VA05064957	1.43
2	1	1.0	2.0	20		20.0	cb/chl	4		10.0								4.0											
							s/q	2																					
2	1	1.0	2.0	20		20.0	cb/chl	4		10.0								4.0				B382582	240.89	242.32	0.114	DUP		VA05064957	1.43
3	3	1.0	3.0	40		1.0	q/chl	2		2.0								5.0				B382583	242.32	243.85	0.165			VA05064957	1.53
6	6	1.0	2.0	20	85	10.0	cb/chl	5		100.0								5.0											
2	3	1.0	2.0	40		6.0	cb/q	4		2.0								5.0				B382584	243.85	244.72	0.644			VA05064957	0.87
4	6	0.2	0.8	80		16.0	cb/chl	5		100.0								5.0											
5	1	1.0	4.5	70	120	4.0	q/chl	4,2		5.0			2.0					5.0	2.0			B382585	244.72	245.36	0.255			VA05064957	0.64
5	6	0.6	2.0	70	125	10.0	cb/chl	5		100.0								4.0											
3	1	3.5	5.5	50		8.0	cb/chl	3		5.0	10.0							1.0				B382586	245.36	246.89	0.19			VA05064957	1.53
							q/s	1																					
4	1	2.0	4.5	45		5.0	q/cb	4	1	10.0	10.0							2.0				B382587	246.89	248.41	0.322			VA05064957	1.52
3	1	1.0	3.0	50		10.0	q/chl	3		10.0			5.0					4.0	2.0			B382588	248.41	249.93	0.099			VA05064957	1.52
3	1	1.0	3.0	50		10.0	q/chl	3		10.0			5.0					4.0	2.0			B382589	248.41	249.93	0.128	PD/CA		VA05064957	1.52
																						B382590	STANDARD 7G		4.45	7G		VA05064957	
5	1	1.0	4.5	35		10.0	q/chl	3	1	3.0			5.0					5.0	2.0			B382591	249.93	251.46	0.773			VA05064957	1.53
							cb/s	2																			same selvage		
8	1	1.5	7.0	35	10	125.0	q/chl	3			6.0							3.0				B382592	251.46	252.98	0.095			VA05064957	1.52
							cb/s	2																					
8	4	0.7	2.0	65	75					8.0								5.0									qtz and carb w/ sulph		
4	1	1.0	4.0	45		1.0	q	2			10.0											B382593	252.98	254.51	0.119			VA05064957	1.53
1	4	1.3	1.3	65		24.0	cb/chl	4		5.0								5.0									all selvage		
5	1	1.0	5.0	50		3.0	q/chl	4,1			5.0											B382594	254.51	256.03	0.185			VA05064957	1.52
1	6	10.0	10.0	62		40.0	cb/chl	3	1	60.0								5.0											
3	4	1.0	2.0	50		150.0	cb/chl	4	1	5.0								5.0				B382595	256.03	257.56	0.191		aspy and py in diff. veins	VA05064957	1.53
1	6	0.5	0.5	85						100.0								5.0											
																						B382596	BLANK		<0.006			VA05064957	
3	1	3.0	6.0	50		20.0	q/chl/cb	4	1	25.0			15.0					2.0				B382597	257.56	259.09	0.13			VA05064957	1.53
1	6	0.5	0.5	70		20.0	q/chl	2		100.0								2.0											
5	1	2.0	6.0	50		30.0	cb/chl/q	3			12.0											B382598	259.09	260.60	0.544			VA05064957	1.51
2	1	1.0	2.0	30		10.0	cb/chl/q	3		10.0								4.0				B382599	260.60	262.12	0.326			VA05064957	1.52
4	3	0.5	2.0	60		30.0	cb/chl	4		5.0								5.0											
2	1	1.0	2.0	40		10.0	q/cb/chl	4		2.0	5.0											B382600	262.12	263.65	0.123			VA05064957	1.53
3	6	1.0	1.4	35		20.0	chl/cb	4		100.0								5.0											
6	1	1.0	6.0	40	50	10.0	q/chl	4			6.0	1.0										B382601	263.65	265.17	0.258			VA05064957	1.52
1	6	0.3	0.3	50		8.0	q	4		100.0								5.0											
							cb/chl	1																					
1	6	0.3	0.3	50		8.0	q	4		100.0								5.0				B382602	263.65	265.17	0.027	DUP	difficult to see	VA05064957	1.52
3	1	1.0	3.0	40	50	20.0	q/chl	4		10.0	5.0							4.0				B382603	265.17	266.70	0.554			VA05064957	1.53
2	6	0.3	0.6	40		40.0	cb/chl	5		100.0								5.0									po appears w/ bt		

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 13 of 14	
DRILL HOLE # : DG05-295C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd. Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		266.70	271.12	GND: Zone of extreme carb and chl alt'n. Rock is 90% v broken to crumbly clay texture. Overall colour is pale greenish grey	2	1	4	2	4	
10		271.42	275.84	GND: Unalt'd GND w/ small qtz veins w/ small silicified selvages. Medium grey. Only small carbonate veinlets at low angle.					1	
10		275.84	281.94	GND: More carbonate content in otherwise unalt'd GND. Causes crumbly sections, up to 40cm long. GND here is somewhat finer-grained, but minerals still visible (1-2mm).					2	
			EOH							

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

PAGE 14 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																							
						Selvages				Sulphides										Oxidation					Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other			From	To					
1	1	1.0	1.0	30						5.0								5.0					B382604	266.70	268.23	1.08			VA05064957	1.53
1	6	0.5	0.5	30						100.0								5.0												
3	1	1.0	3.0	50	40	4.0	q/chl	2			10.0												B382605	268.23	269.75	0.115			VA05064957	1.52
1	6	0.9	0.9	60		20.0	cb/chl	4		60.0								5.0										py in 0.4cm lens		
3	1	2.0	4.5	50		4.0	q/cb	4		5.0	5.0							3.0					B382606	269.75	271.12	0.053			VA05064957	1.37
2	6	1.5	2.5	70		10.0	q/cb	4		60.0								5.0												
1	1	12.0	12.0	70		40.0	cb/chl	4		15.0								3.0					B382607	271.12	271.42	0.342			VA05064957	0.30
							q	1																						
5	1	1.0	5.0	50	85	1.0	q	3			5.0							2.0					B382608	271.42	272.80	0.086			VA05064957	1.38
5	1	1.0	5.0	50	85	1.0	q	3			5.0							2.0					B382609	271.42	272.80	0.068	PD/CA		VA05064957	1.38
																							B382610	STANDARD 3C		0.089	3C	alt'n to bt w/in veins	VA05064957	
4	1	1.5	4.5	30	50	1.0	q/chl	3,1			3.0												B382611	272.80	274.32	0.397			VA05064957	1.52
1	6	0.3	0.3	155						60.0	10.0							5.0												
4	1	1.5	5.0	45	60	2.0	q	4		10.0	5.0							4.0					B382612	274.32	275.84	0.119			VA05064957	1.52
3	1	1.0	3.0	35		2.0	q/chl	3			10.0		4.0					3.0	1.0				B382613	275.84	277.37	0.068			VA05064957	1.53
3	4	0.6	1.8	25		30.0	cb	3		10.0								5.0												
1	3	0.5	0.5	65		1.0	cb/chl	2		10.0								5.0												
5	1	1.5	5.0	60	25	2.0	q/cb	4															B382614	277.37	278.89	0.544			VA05064957	1.52
							b	2																						
4	4	0.5	1.2	10	35	20.0	cb	2		5.0								5.0												
5	1	2.0	4.5	30	40	5.0	cb/q	3			5.0												B382615	278.89	280.21	0.155			VA05064957	1.32
2	3	10.0	12.0	70		2.0	cb/chl	2		15.0	2.0							5.0										sulph vein zigzags btwn 10 and 60° (sheared).		
1	6	0.5	0.5	10	60	20.0	cb	4		50.0								5.0										po w/ bt		-
																							B382616	BLANK		<0.005			VA05064957	
4	1	1.0	4.0	50		1.0	q	2			5.0												B382617	280.41	281.94	0.066			VA05064957	1.53
2	3	0.3	0.6	35		1.0	q/cb	3		5.0								5.0												
																									E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-296C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 916m

BEARING: 000 | DIP: -50°

DATE STARTED: 19-Jul-05 | DATE COMPLETED: 21-Jul-05

COORD SYSTEM: NAD 27: EASTING: 459153 NORTHING: 7099840

COORD SYSTEM: NAD 83: EASTING: 459034 NORTHING: 7100025

NAD 27 (CORRECTED for historic grid): EASTING: 459123 NORTHING: 7099850

LOGGED BY: Terry Croteau

SECTION LINE(historic grid): 459125E

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden: 4.57m

Deviation:

Casing: 4.57m

Core Size: HQ & NQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381181 to B381238

Requisition #: MASP448STRGOL.05Q Date Shipped: 5-Aug-05

Lab Record #: VA05066350 Date Received: 12-Aug-05

Sample Sequence: B381239 to B381384

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05067824 Date Received: 12-Aug-05

Sample Sequence: B281385 to B381387

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05069644 Date Received: 21-Aug-05

Duplicates:	B381182, B381202, B381222, B381242, B381262, B381282, B381302, B381322, B381342, B381362, B381382,
Preparation Duplicate/ Check Assay:	B381189, B381209, B381229, B381249, B381269, B381289, B381309, B381329, B381349, B381369
Standards:	B381190 (2B), B381210(5E), B381230(1A), B381250(7G), B381270(3C), B381290(4D), B381210(1A), B381230(7G), B381250(6F), B381270(4D)
Blanks:	B381196, B381216, B381236, B381256, B381276, B381296, B381316, B381336, B381356, B381376

FROM	TO	LITHOLOGY
4.57	198.12	MSED (QZZ; Qtz Monzonite)

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
61.0	335.0	-48.3	001.0	002.0
121.9	338.6	-49.3	004.6	005.6
198.1	339.8	-50.4	005.8	006.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE:	PAGE	of 10
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
1	0.00 - 4.57	0.00	4.57	Casing with 9% recovery. MSED and GND, likely from boulders.						
80	4.57 - 30.17			MSED - Derived from pelitic to arenaceous sediment. Foliated, may be phyllitic or carbonaceous						
		4.57	9.14	MSED - Pervasive lim and lim staining on frac faces. Core is broken and recovery is poor. Foliation difficult to determine because of broken core. Foliation @4.57m is at 30-32° TCA. @6.10m, -> 50-52°; @7.62m -> 15-20°; @7.62m -> 0.2cm aspy vein @ 60° to CA	3	2	1	1	1	
80		9.14	18.29	MSED: Same as above, but more competent with better recovery. Boudins present throughout indicating increased shear. Foliation @ 9.14m -> 25-30°; @10.67m -> 30-35°; @ 12.19m -> 35-40°; @13.72m -> 35-40°; @15.24m -> 30-35°; @16.76m -> 35-40°	3	2	1	1	1	
80		18.29	21.80	MSED - Lim continues pervasively and on frac faces. Boudins are present, but reduced in frequency. Foliation @ 18.29m -> 20-25°; @19.81m -> 35-40°; @21.34m -> 30-32°.	3	2	1	1	1	
80		21.80	24.65	Silicious MSED. Dark grey colour, pervasive lim is reduced. Foliation @ 21.80m -> 30-32° @22.86m -> 25-30° @24.38m -> 20-22° @18.29m - 1cm aspy vein @ 20° to CA, 90% aspy, 2% py	2				1	
80		24.65	30.17	MSED - Lim pervasive and on frac faces. Argillic alt'n increased. Foliation is generally at lower angles. Foliation @ 24.65m-> 35-37 @ 25.91m ->22-25° @ 27.43m -> 22-25° @28.96m -> 22-25° @28.26m - 30cm sandstone bed. Brown, oxidized, 85% qtz, 10% K-feld, Laminae @ 22-25° to CA. Contact with MSED @ 22°.	2	3	1	2	2	
12	30.17 - 32.57	30.17	32.57	GND Dyke. 40% qtz 20% plag. Grey, with pervasive lim. Frac faces are stained dark red. Euhedral aspy crystals can be found within the red staining. Veins present are small (< 0.2 cm). Uphole contact not visible. Downhole contact @ 35° to CA	3					
80	32.57 - 120.40	32.57	37.50	MSED - Dark Grey. Pervasive lim is reduced, but still prevalent on frac faces. Carb veinlets increase in number. Foliation @ 32.57m -> 35-37° @ 33.53m -> 35-37° @35.05m -> 30-32° @36.58m -> 25-30°	2	3	1	1	2	
80		37.50	45.72	Silicious MSED - Minor pervasive lim, also reduced on frac faces. Increase in number of veins as well as size and mineralization. Boudins present throughout. Foliation @37.50m -> 22-25° @38.10m -> 40-42° @39.62m -> 25-30° @41.15m -> 25-30° @42.67m -> 25-27° @44.20m -> 27-30°	1				1	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration, 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
0																						B381181	0.00	4.57	**0.014**			VA05066350	4.57
0																						B381182	0.00	4.57	**0.027**	DUP		VA05066350	4.57
0																						B381183	4.57	6.10	**0.022**			VA05066350	1.53
0																						B381184	6.10	7.62	**0.025**			VA05066350	1.52
1	6	0.2	0.2	60									40.0									B381185	7.62	9.14	**0.05**			VA05066350	1.52
0																						B381186	9.14	10.67	**0.005**			VA05066350	1.53
0																						B381187	10.67	12.19	**0.015**			VA05066350	1.52
0																						B381188	12.19	13.72	**<0.005**			VA05066350	1.53
0																						B381189	12.19	13.72	**<0.005**	PD/CA		VA05066350	1.53
																						B381190	STANDARD 2B		**3.07**	2B		VA05066350	
0																						B381191	13.72	15.24	**0.047**			VA05066350	1.52
0																						B381192	15.24	16.76	**0.008**			VA05066350	1.52
2	1	2.0	3.0	30						0.1												B381193	16.76	18.29	**0.005**			VA05066350	1.53
2	1	2.0	4.0	30						0.1												B381194	18.29	19.81	**0.022**			VA05066350	1.52
1	1	0.2	0.2	30																		B381195	19.81	21.34	**<0.005**			VA05066350	1.53
																						B381196	BLANK		**<0.005**			VA05066350	
0																						B381197	21.34	21.80	**0.011**			VA05066350	0.46
1	6	1.0	1.0	25						2.0			60.0									B381198	21.80	22.06	**0.35**			VA05066350	0.26
0																						B381199	22.06	22.86	**0.021**			VA05066350	0.80
1	6	0.1	0.1	25																		B381200	22.86	24.38	**0.007**			VA05066350	1.52
0																						B381201	24.38	24.65	**<0.005**			VA05066350	0.27
0																						B381202	24.38	24.65	**0.006**	DUP		VA05066350	0.27
0																						B381203	24.65	25.91	**0.006**			VA05066350	1.26
1	1	2.0	2.0																			B381204	25.91	27.43	**0.018**		Qtz eyes	VA05066350	1.52
0																						B381205	27.43	28.96	**0.148**			VA05066350	1.53
2	1	0.4	0.8	40																		B381206	28.96	30.17	**0.017**			VA05066350	1.21
2	3	1.0	1.0	20																		B381207	30.17	30.48	**0.075**			VA05066350	0.31
4	6	0.1	0.4	60									40.0					70.0				B381208	30.48	32.00	**0.167**			VA05066350	1.52
4	6	0.1	0.4	60									40.0					70.0				B381209	30.48	32.00	**0.124**	PD/CA		VA05066350	1.52
																						B381210	STANDARD 5E		**1.355**	5E		VA05066350	
2	1	0.5	1.0	50									0.1									B381211	32.00	32.57	**0.024**			VA05066350	0.57
0																						B381212	32.57	33.53	**0.01**			VA05066350	0.96
2	1	0.2	0.4	20																		B381213	33.53	35.05	**0.04**			VA05066350	1.52
0																						B381214	35.05	36.58	**0.008**			VA05066350	1.53
1	6	0.2	0.2	65		2.0	q	4	0	3.0			0.1					90.0				B381215	36.58	37.50	**0.012**			VA05066350	0.92
																						B381216	BLANK		**<0.005**			VA05066350	
1	6	3.0	3.0	60									40.0									B381217	37.50	38.10	**<0.005**		Crosscuts foliation	VA05066350	0.60
3	1	0.5	0.9	40																		B381218	38.10	39.99	**0.057**		bt in vein	VA05066350	1.89
1	1	28.0	28.0	30									5.0									B381219	39.99	40.27	**0.076**		bt in vein	VA05066350	0.28
3	6	0.1	0.3	60									10.0									B381220	40.27	41.15	**0.006**		Crosscuts foliation	VA05066350	0.88
2	4	0.1	0.2	60																		B381221	41.15	42.67	**0.032**		Crosscuts foliation	VA05066350	1.52
2	4	0.1	0.2	60																		B381222	41.15	42.67	**0.019**	DUP		VA05066350	1.52
2	6	0.1	0.2	60		2.0	b	4	0				3.0									B381223	42.67	44.20	**0.029**		Aspy in selvage	VA05066350	1.53

DRILL LOG LEGEND - P1	DATE:	PAGE 3 of 10	
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		45.72	56.39	QZZ (80%) with silicious MSED (20%). MSED dark grey, purple, green, foliation difficult to see. May be silicfied hornfels. QZZ light grey, no foliation and an increase in the number and size of qtz veins. Lim staining is reduced to fracture faces only. Frac faces also contain euhedral py or aspy crystals. Foliation @ 45.72m -> 30-32°, @47.24m -> 30-32°, @48.77m -> 30-32°, @50.29m -> 25-30°, @51.82m -> 40-42°, @53.34m -> 35-40°, @54.86m -> 35-37°	1	1	1	1	1	
80		56.39	67.06	MSED (70%) dark grey with prominent foliation. QZZ (30%) associated with veins, possibly related as selvages. MSED contains diss aspy and po throughout. Foliation @65.39m -> 45-50°, @57.91m -> 45-50°, @59.44m -> 45-50°, @60.96m -> 35-40°, @62.48m -> 35-40°, @64.01m -> 45-50°, @65.53m -> 35-40°. Lim staining on frac faces reduced to 30%.	1	2	2	1	1	
80		67.06	68.58	MSED HFLS - Easily scratchable. Violet, green, grey color. Qtz veining reduced, low angle (<10°) crosscuts foliation. Diss py present. Foliation @ 30-35° to CA.	1	3	2	2	1	
80		68.58	73.57	QZZ - Light grey green color. Increase in vein frequency and size as well as sulphide content. Visible residual foliation @ 70.90m -> 30° to CA			2		1	
80		73.57	80.20	Silicious MSED. Dark grey, veining is predominantly 0.2cm qtz veins with bt selvages that contain 10-20% aspy. Trace aspy can also found between foliations. Foliation @73.57m -> 35-40°, @74.68m -> 50-52°, @76.20m -> 40-45°, @77.72m -> 40-45°, @79.25m -> 45.50°		1	1		1	
80		80.20	81.16	QZZ. Light grey, 80% qtz, no visible foliation. Veins are larger, up to 9cm, and increase in number			1		1	
		81.16	83.82	Silicious MSED. Dark grey, fewer sulphide veins than previous MSED interval. Diss aspy present after 82.30m. Foliation @81.16m -> 45-50°, @82.30m -> 35-40°, crenulated		1	1		1	
80		83.82	88.39	QZZ. Light grey. Increase in 0.2cm aspy veins as well as diss aspy. Qtz veins nearly absent. Minor lim staining on frac faces (20%).	1		1		1	
80		88.39	92.63	Silicious MSED. Dark grey, minor lim on frac faces (15%). Diss aspy present. Foliation @88.39m -> 30-35°, @89.92m -> 30-35°, @91.44m -> 30-35°. Contact with QZZ @ 30°.	1	1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
3	6	0.1	0.3	60		1.0	q	4	0				3.0									B381224	44.20	45.72	0.013		Aspy in selvage /Vein Crosscuts	VA05066350	1.52
4	6	0.1	0.4	60									10.0									B381225	45.72	47.24	0.142		Crosscuts foliation	VA05066350	1.52
3	1	5.0	11.0	50	30								0.1									B381226	47.24	48.77	0.025			VA05066350	1.53
1	6	0.1	0.1	125									5.0														Crosscuts foliation		
2	6	0.1	0.2	125									5.0									B381227	48.77	50.29	0.052		Crosscuts foliation	VA05066350	1.52
3	6	0.1	0.3	125									5.0									B381228	50.29	51.82	0.411		Crosscuts foliation	VA05066350	1.53
3	6	0.1	0.3	125									5.0									B381229	50.29	51.82	0.414	PD/CA		VA05066350	1.53
																						B381230	STANDARD 1A		0.83	1A		VA05066350	
1	1	2.0	2.0	50							3.0		3.0									B381231	51.82	53.34	0.015			VA05066350	1.52
2	6	0.2	0.4	60									10.0									B381232	53.34	54.86	0.166			VA05066350	1.52
	4	0.1		15	30																	B381233	54.86	56.39	0.083		Veinlets	VA05066350	1.53
1	1	3.0	40.0							3.0	3.0											B381234	56.39	57.91	0.023			VA05066350	1.52
1	1	5.0	5.0	30							1.0		1.0									B381235	57.91	59.44	0.015			VA05066350	1.53
																						B381236	BLANK		<0.005			VA05066350	
1	6	0.5	0.5							6.0			5.0									B381237	59.44	60.96	0.099			VA05066350	1.52
3	1	1.0	3.0	10	20								0.1									B381238	60.96	62.48	0.702			VA05066350	1.52
3	1	0.1	0.3	60		1.0	b	5	0				0.1									B381239	62.48	64.01	0.022		Aspy in selvage/ crosscut fol	VA05067824	1.53
2	1	25.0	35.0	25	35								0.1									B381240	64.01	65.53	0.061			VA05067824	1.52
0																						B381241	65.53	67.06	0.026			VA05067824	1.53
0																						B381242	65.53	67.06	0.041	DUP		VA05067824	1.53
1	1	1.5	1.5	125									10.0									B381243	67.06	68.58	0.026			VA05067824	1.52
3	1	1.5	2.5	20	##						1.0	0.1										B381244	68.58	70.10	0.04			VA05067824	1.52
4	1	8.0	18.0	40									0.1					90.0				B381245	70.10	71.63	0.041			VA05067824	1.53
2	1	5.0	7.0	60									0.1									B381246	71.63	73.15	0.015			VA05067824	1.52
0																						B381247	73.15	73.57	0.013			VA05067824	0.42
1	1	1.0	1.0	55							1.0											B381248	73.57	74.68	0.005			VA05067824	1.11
1	1	1.0	1.0	55							1.0											B381249	73.57	74.68	0.005	PD/CA		VA05067824	1.11
																						B381250	STANDARD 7G		4.73	7G		VA05067824	
1	1	3.0	3.0	50							1.0											B381251	74.68	76.20	0.014			VA05067824	1.52
3	1	0.1	0.3	55		1.0	q/b	5	0				1.0									B381252	76.20	77.72	0.013		Aspy in selvage	VA05067824	1.52
1	1	1.0	1.0	55		1.0	q/b	5	0				5.0									B381253	77.72	79.25	0.081		Aspy in selvage	VA05067824	1.53
2	3	1.0	1.2	55		0.5	b	4	0				3.0									B381254	79.25	80.20	0.012			VA05067824	0.95
3	1	9.0	15.0	50		2.0	chl	2	0	0.1	0.1											B381255	80.20	81.16	0.011			VA05067824	0.96
																						B381256	BLANK		<0.005			VA05067824	
4	4	0.1	0.4	30	35																	B381257	81.16	82.30	0.035			VA05067824	1.14
4	6	0.1	0.4	60									3.0									B381258	82.30	83.82	0.013			VA05067824	1.52
5	6	0.2	0.6	60									10.0									B381259	83.82	85.34	0.034		Crosscuts foliation	VA05067824	1.52
9	6	0.2	1.0	60									10.0									B381260	85.34	86.87	0.048		Crosscuts foliation	VA05067824	1.53
3	6	0.1	0.3	60									5.0									B381261	86.87	88.39	0.073			VA05067824	1.52
3	6	0.1	0.3	60									5.0									B381262	86.87	88.39	0.084	DUP		VA05067824	1.53
2	6	0.1	0.2	60		0.2	b	4	0	1.0			1.0									B381263	88.39	89.92	0.07		Aspy in selvage	VA05067824	1.52
1	6	0.2	0.2	60		0.2	q/b	3	0				1.0									B381264	89.92	91.44	0.01			VA05067824	1.19

DRILL LOG LEGEND P1	DATE:	PAGE 5 of 10	
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		92.63	93.75	MSED: Pervasive lim present until 92.96m. Lim staining on frac faces increased (60%). 80% of veins crosscut foliation @30-32 °		1				
80		93.75	104.49	Silicious MSED. Dark grey, few qtz veins. Lim staining on fractures (60%). Foliation @93.75m >30-35°, @94.49m -> 30-35°, @96.01m -> 30-32°, @97.54m -> 25-27°, @99.06m -> 40-42°, @100.58m -> 40-42°, @102.11m -> 45-50°, @103.63m -> 35-40°. @102.11m - 12cm grey qtz vein @ 45° to CA.	1	2	1		1	
80		104.49	118.87	QZZ. Light grey to grey, very little visible foliation. Interval contains a might higher concentration of sulphides than all previous intervals. Aspy veins are dominant type, as well as py. Very few veins (10%) are quartz. @105.86m - 3cm massive aspy vein. No contact visible. Vein is broken and may be larger @106.98m - 1cm massive aspy vein + sphalerite @25° to CA @107.31m - 10cm massive sulphide vein. 25% aspy, 45% py + qtz @ 60° to CA @108.58m - 1.5cm massive aspy vein @45° to CA - 1cm sphalerite vein @45° to CA @112.50m - broken massive aspy and py vein. Core recovery is 67%, vein has a minimum size of ~10cm and may be 15-20cm or greater. No qtz present. Vein is 80% aspy, 20% py. Picture 100-0059 and 100-0060		1	1			
80		118.87	120.40	QZZ/HFLS Transition between QZZ and GND dyke. Light grey QZZ with interlayered HFLS. Diss aspy in QZZ. Foliation in HFLS @35° to CA.		2	2		1	
12	120.40 - 121.92	120.40	121.92	GND - 40% qtz, 20% plag, 15% bt, 15% hbl. Dark grey, fine grained. Contains higher than usual amounts of hbl compared to other holes. Few qtz or sulphide veins. Cb veining increased. No visible contacts with surrounding core.					1	
80	121.92 - 198.12	121.92	124.97	Silicious MSED. Dark grey. Foliation at beginning of interval @20° to CA grading to 45° after 123.44m. No indication of contact with GND		2	1	1		
80		124.97	128.64	QZZ. Light grey, with relic foliation visible @45° to CA. Sulphide veinlets crosscut, as do low angle cb veinlets (10-30° to CA)			1			
80		128.64	130.86	Silicious MSED. Dark grey. Qtz veins follow foliations, and cb veining is reduced. Foliation @128.64m -> 45-47°, @129.54m -> 40-42°		1	1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	6	0.2	0.2	60		0.2	b	4	0				0.1									B381265	91.44	92.63	<0.005			VA05067824	1.19
4	4	0.2	0.8	20																		B381266	92.63	93.75	<0.005			VA05067824	1.12
2	1	1.0	2.0	70								3.0	1.0									B381267	93.75	94.49	0.079		Crosscuts foliation	VA05067824	0.74
2	1	1.0	1.5	35							0.1											B381268	94.49	96.01	<0.005			VA05067824	1.52
2	1	1.0	1.5	35							0.1											B381269	94.49	96.01	0.005	PD/CA		VA05067824	1.52
																						B381270	STANDARD 3C		0.096	3C		VA05067824	
4	6	0.1	0.4	55									1.0									B381271	96.01	97.54	0.079			VA05067824	1.53
	4	0.1		30																		B381272	97.54	99.06	0.014		Veinlets	VA05067824	1.52
3	1	1.0	1.7	40							0.1											B381273	99.06	100.58	0.017			VA05067824	1.52
1	1	8.0	8.0	70									5.0						90.0			B381274	100.58	102.11	0.01			VA05067824	1.53
1	1	12.0	12.0	40									1.0									B381275	102.11	103.63	0.019			VA05067824	1.52
																						B381276	BLANK		<0.005			VA05067824	
2	4	0.1	0.2	50																		B381277	103.63	104.49	0.017			VA05067824	0.86
3	1	2.0	3.0	50																		B381278	104.49	105.16	0.005			VA05067824	0.67
0																						B381279	105.16	105.86	0.013			VA05067824	0.70
1	6	3.0	3.0							10.0			80.0									B381280	105.86	105.93	2.79			VA05067824	0.07
3	1	5.0	8.0																			B381281	105.93	106.98	0.141			VA05067824	1.05
3	1	5.0	8.0																			B381282	105.93	106.98	0.157	DUP		VA05067824	0.33
1	6	1.0	1.0	25									80.0		10.0							B381283	106.98	107.31	0.153			VA05067824	0.25
1	6	10.0	10.0	65						45.0			25.0									B381284	107.31	107.56	1.06			VA05067824	
0																						B381285	107.56	108.20	0.057			VA05067824	0.64
0																						B381286	108.20	108.58	0.165			VA05067824	0.38
2	6	1.5	2.5	45									90.0		90.0							B381287	108.58	108.80	3.31			VA05067824	0.22
1	6	0.2	0.2	70						1.0												B381288	108.80	109.73	0.052			VA05067824	0.93
1	6	0.2	0.2	70						1.0												B381289	108.80	109.73	0.049	PD/CA		VA05067824	0.93
																						B381290	STANDARD 4D		0.452	4D		VA05067824	1.25
11	4	0.2	2.2	70	5																	B381291	109.73	111.25	0.037			VA05067824	0.10
1	6	0.2	0.2	60									10.0									B381292	111.25	112.50	0.108			VA05067824	1.70
1	6									20.0			80.0									B381293	112.50	112.60	3.53			VA05067824	1.52
5	4	0.2	1.0	55									5.0		5.0							B381294	112.60	114.30	0.074			VA05067824	1.70
3	1	2.0	3.0	30						1.0								90.0				B381295	114.30	115.82	0.005			VA05067824	1.52
																						B381296	BLANK		<0.005			VA05067824	
3	1	4.0	7.0	10	45					1.0			1.0									B381297	115.82	117.35	<0.005			VA05067824	1.53
1	1	4.0	4.0	10						1.0			1.0									B381298	117.35	118.87	0.018			VA05067824	1.52
5	6	0.1	0.5	57									0.1									B381299	118.87	120.40	0.113			VA05067824	1.53
2	1	2.0	2.5	60																		B381300	120.40	121.92	<0.005			VA05067824	1.52
3	1	1.0	2.0	40						1.0												B381301	121.92	123.44	<0.005			VA05067824	1.52
3	1	1.0	2.0	40						1.0												B381302	121.92	123.44	<0.005	DUP		VA05067824	1.52
	4			10	20																	B381303	123.44	124.97	<0.005		Veinlets	VA05067824	1.53
1	1	1.0	1.0	55							3.0											B381304	124.97	126.49	0.006			VA05067824	1.52
4	6	0.1	0.4	60		0.2	b	0					1.0									B381305	126.49	128.02	0.006		Aspy in selvage	VA05067824	1.53
2	6	0.1	0.2	60		0.2	b	0					0.1									B381306	128.02	128.64	<0.005		Aspy in selvage	VA05067824	0.62
0																						B381307	128.64	129.54	<0.005			VA05067824	0.90
1	1	5.0	5.0	50									0.1									B381308	129.54	130.86	<0.005			VA05067824	1.32

DRILL LOG LEGEND P1	DATE:	PAGE 1 of 10		
DRILL HOLE # : DG05-296C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		130.86	131.82	QZZ. Light grey green, minor chl alt present giving green color. Py crystals on frac faces. Qtz, cb and sulphide veins crosscut.			2			
80		131.82	133.29	MSED. Grey brown. Py on frac faces. Soft, easy to scratch. Foliation @38-40°		2	2	1	1	
80		133.29	142.20	QZZ - Light grey. Residual foliation @134.11m -> 50°, @140.71m -> 35-45°. Increase in qtz/sulphide veins and sulphide concentrations. Core is broken and fractured until 141.03m where it regains competency. @134.61m - 4cm massive aspy vein @80° to CA @140.21m - 4cm massive sulphide vein @5° to CA; 40% sph, 20% py @140.39m - 8cm massive sulphide vein @50° to CA; 40% aspy, 30% sph, 20% py. Also present in the vein is a vug containing lead grey delicate acicular crystals. These are likely some form of Sb-Pb sulphide. Possibly stibnite, but more likely boulangerite or jamesonite. See photo. @134.61m marks the beginning of a zone of massive sulphide veining continuing until 158.40m. Veining may be related to the QZZ and very silicious MSED in the interval. Sulphides found throughout this core are more often found in QZZ than in MSED.		1	2			
80		142.20	144.31	Silicious MSED - Dark grey. Sulphides are almost absent in this interval. Foliation @142.20m -> 30-32°, @143.26m -> 37-40°						
80		144.31	144.63	APL dyke. Uphole contact @20° to CA. Downhole @35° to CA. Diss py and aspy present.						
80		144.63	146.30	QZZ - Light grey. No visible foliation. @145.46m - 7cm sulphide vein @55° to CA, 50% py, 10% aspy, 5% sph						
80		146.30	150.76	Silicious MSED - Dark grey, reduced veinage and sulphide content. Foliation @146.30m -> 45-47°, @147.83m -> 30-35°, @149.35m -> 45-47°		1	1	1	1	
80		150.76	151.48	QMON - Dark grey-green. 25% K-spar, 25% plag, 10% qtz, 15% bt. Uphole contact @80° to CA. Downhole contact not visible		1	3	1		
80		151.48	152.40	MSED - Dark grey. Foliation @20-25°. Silicious		1	1	1	1	
80		152.40	167.64	QZZ - Light grey to grey. There is an increase in sulphide veining. Foliation @152.40m -> 30-32°, @161.54m -> 32-35°. @154.67m - 60cm gouge @30° to CA @156.50m - 30cm grey qtz vein. No visible contact. 1% sulphides @156.80m - 2cm massive sulphide vein @60° to CA, 90% py, 10% aspy @158.15m - 15+ cm massive sulphide vein. Broken, with no visible contacts. Possibly 15-20cm or more in width. Sulphide concentrations range from 50% py & 50% aspy to 30% py & 70% aspy. The difference in concentrations could indicate more than one vein. Partial reconstruction yielded a contact angle near 75° @166.48m - 50cm gouge with QZZ fragments @45° to CA			1			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	5.0	5.0	50									0.1									B381309	129.54	130.86	0.005	PD/CA		VA05067824	1.32
																						B381310	STANDARD 1A		0.916	1A		VA05067824	
2	1	1.0	2.0	30						0.1												B381311	130.86	131.82	0.007			VA05067824	0.96
0																						B381312	131.82	132.59	0.008			VA05067824	0.77
0																						B381313	132.59	133.29	<0.005			VA05067824	0.70
0																						B381314	133.29	134.11	<0.005			VA05067824	0.82
0																						B381315	134.11	134.61	0.005			VA05067824	0.50
																						B381316	BLANK		<0.005			VA05067824	
1	6	4.0	4.0	80									40.0		20.0							B381317	134.61	134.71	0.18			VA05067824	0.10
2	6	0.2	0.2	50											10.0							B381318	134.71	135.64	0.011			VA05067824	0.93
2	1	0.2	0.4	20																		B381319	135.64	137.16	0.008			VA05067824	1.52
2	1	0.2	0.1	40																		B381320	137.16	138.68	0.013			VA05067824	1.52
2	6	0.1	0.2	55																		B381321	138.68	140.21	0.016			VA05067824	1.53
2	6	0.1	0.2	55																		B381322	138.68	140.21	0.016	DUP		VA05067824	1.53
1	6	4.0	4.0	5						20.0					40.0							B381323	140.21	140.39	0.177		Massive Sulphides	VA05067824	0.18
1	6	8.0	8.0	50						20.0			40.0		30.0		0.1					B381324	140.39	140.61	2.08		Massive Sulphides	VA05067824	0.22
1	1	3.0	3.0	60									0.1									B381325	140.61	141.73	0.007			VA05067824	1.12
2	1	2.0	4.0	40									0.1									B381326	141.73	142.20	0.015			VA05067824	0.47
0																						B381327	142.20	143.26	0.006			VA05067824	1.06
2	1	2.0	3.0	40							0.1											B381328	143.26	144.31	<0.005			VA05067824	1.05
2	1	2.0	3.0	40							0.1											B381329	143.26	144.31	<0.005	PD/CA		VA05067824	1.05
																						B381330	STANDARD 7G		4.51	7G		VA05067824	
0																						B381331	144.31	144.63	0.008			VA05067824	0.32
2	1	3.0	5.0	40						0.1			0.1									B381332	144.63	145.46	0.013			VA05067824	0.83
1	6	7.0	7.0	55						50.0			10.0		5.0							B381333	145.46	145.53	4.52		Massive sulphides	VA05067824	0.07
0																						B381334	145.53	146.30	0.014			VA05067824	0.77
1	3	0.5	0.5	50																		B381335	146.30	147.83	<0.005			VA05067824	1.53
																						B381336	BLANK		<0.005		Crosscuts foliation	VA05067824	
1	6	0.5	0.5	55						1.0			5.0		0.1							B381337	147.83	149.35	0.014		Veinlets/crosscuts foliation	VA05067824	1.52
	4	0.1		10	25																	B381338	149.35	150.76	<0.005			VA05067824	1.41
0																						B381339	150.76	151.48	0.015			VA05067824	0.72
1	4	0.2	0.2	30																		B381340	151.48	152.40	<0.005		Crosscuts foliation	VA05067824	0.92
0																						B381341	152.40	153.92	<0.005			VA05067824	1.52
0																						B381342	152.40	153.92	<0.005	DUP		VA05067824	1.52
1	1	2.0	2.0	30						0.1												B381343	153.92	154.67	0.019			VA05067824	0.75
0																						B381344	154.67	155.45	0.026		Gouge	VA05067824	0.78
3	6	0.1	0.3	45						1.0												B381345	155.45	156.50	0.019			VA05067824	1.05
1	1	30.0	30.0							1.0			1.0									B381346	156.50	156.80	0.027			VA05067824	0.30
1	6	2.0	2.0	60						90.0			10.0									B381347	156.80	156.87	5.69		Massive Sulphides	VA05067824	0.07

DRILL LOG LEGEND P1	DATE:	PAGE 9 of 10	
DRILL HOLE # : DG05-296C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		167.64	172.21	MSED - Less silicious than most previous intervals. 80% of the veins are carbonate. Foliation @167.64m -> 32-35°, @169.16m -> 22-25°, @170.69m -> 32-33°, @168.63m, MSED is brecciated and cemented by cb, until 169.32m, where it contacts the MSED @40° to CA		2	2	2	1	
80		172.21	175.44	Silicious HFLS. Grey to dark grey with violet and green banding. Veining is nearly absent. Uphole contact with MSED @40° to CA. Foliation @172.21m -> 40-42°, @173.74m -> 45-50°		2	3	1	1	
80		175.44	187.90	QZZ and HFLS - Light grey with violet and green banding. 80% of interval is QZZ with intermittent bands of HFLS, the largest being 85cm @182.03m. Foliation is visible in HFLS @40-45° to CA. @172.6m - Cave. Pebbles include MSED and massive sulphides - no sample @185.80m - 3cm qtz/cb/sulphide vein @ 40° to CA. 60% aspy		2	2			
80		187.90	191.56	Silicious MSED + HFLS: Dark grey to black. Minor HFLS (5%) containing green and violet banding. Foliation @187.90m-> 45-50°, @188.98m -> 60-62°, @190.50m -> 60-62°		3	2	2	1	
80		191.56	192.60	QZZ - Light grey, no visible foliation. @192.40m - 3cm massive sulphide vein @40° to CA. 20% aspy, 20% py						
80		192.60	198.12	Silicious MSED - Light grey-green. More Chl than most intervals. Foliation @192.60m -> 45-47°, @193.55m -> 60-62°, @195.07m -> 40-42°, @196.60m -> 40-42° @197.92m - 1cm sphalerite vein @40° to CA @198.02m - 10cm QMON						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

PAGE 10 of 10

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL:														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
	1									0.1												B381348	156.87	158.15	0.056		Broken pieces	VA05067824	1.28
	1									0.1												B381349	156.87	158.15	0.057	PD/CA		VA05067824	1.28
																						B381350	STANDARD 6F		2.82	6F		VA05067824	
1	6	15.0	15.0	75						50.0			50.0									B381351	158.15	158.30	15.25		Massive Sulphides	VA05067824	0.15
3	6	0.2	0.4	65						15.0								40.0				B381352	158.30	160.02	0.226			VA05067824	1.72
2	6	0.1	0.2	30									1.0									B381353	160.02	161.54	0.084			VA05067824	1.52
2	3	1.0	1.5	50						0.1			0.1									B381354	161.54	163.07	0.03			VA05067824	1.53
0																						B381355	163.07	164.59	<0.005			VA05067824	1.52
																						B381356	BLANK		<0.005			VA05067824	
	1																					B381357	164.59	166.12	0.008		Broken pieces	VA05067824	1.53
	1																					B381358	166.12	167.64	0.248		Broken pieces	VA05067824	1.52
5	1	1.5	4.5	50									10.0									B381359	167.64	169.16	0.212			VA05067824	1.52
3	1	2.0	2.5	30							0.1											B381360	169.16	170.69	<0.005			VA05067824	1.53
1	4	1.0	1.0	150																							Crosscut foliation		
3	1	1.0	1.7	50																		B381361	170.69	172.21	0.009			VA05067824	1.52
																						B381362	170.69	172.21	0.01	DUP		VA05067824	1.52
1	1	1.5	1.5	60																		B381363	172.21	173.74	0.075			VA05067824	1.53
5	1	1.0	2.5	60																		B381364	173.74	175.44	<0.005			VA05067824	1.70
1	1	2.0	2.0	40																		B381365	175.44	176.78	0.015			VA05067824	1.34
	4			10	20																	B381366	176.78	178.31	0.083		veinlets	VA05067824	1.53
	4			10	20																	B381367	178.31	179.83	0.038		veinlets	VA05067824	1.52
4	1	1.0	3.5	58									1.0									B381368	179.83	181.36	0.021			VA05067824	1.53
4	1	1.0	3.5	58									1.0									B381369	179.83	181.36	0.022	PD/CA		VA05067824	1.53
																						B381370	STANDARD 4D		0.446	4D		VA05067824	
2	1	1.0	1.5	45																		B381371	181.36	182.88	0.042			VA05067824	1.52
2	1	2.0	3.0	30									0.1									B381372	182.88	184.40	0.024			VA05067824	1.52
1	6	3.0	3.0	40									60.0									B381373	184.40	184.80	3.47		Massive sulphides	VA05067824	0.40
2	1	2.0	3.0	30									0.1									B381374	184.80	185.93	0.035			VA05067824	1.13
	4			30	60																	B381375	185.93	187.45	0.028		veinlets	VA05067824	1.52
																						B381376	BLANK		<0.005			VA05067824	
0																						B381377	187.45	187.90	0.006			VA05067824	0.45
1	1	6.0	6.0	60																		B381378	187.90	188.98	0.162			VA05067824	1.08
3	4	0.5	0.7	20																		B381379	188.98	190.50	0.596			VA05067824	1.52
0																						B381380	190.50	191.56	0.306			VA05067824	1.06
3	6	0.1	0.3	45									1.0									B381381	191.56	192.40	0.013			VA05067824	0.84
3	6	0.1	0.3	45									1.0									B381382	191.56	192.40	0.009	DUP		VA05067824	0.84
1	6	3.0	3.0							2.0		3.0	10.0									B381383	192.40	192.60	1.345		Massive Sulphides	VA05067824	0.20
0																						B381384	192.60	193.55	<0.005			VA05067824	0.95
1	1	3.0	3.0	45									0.1									B381385	193.55	195.07	<0.005			VA05069644	1.52
1	4	1.5	1.5	25																		B381386	195.07	196.60	0.073			VA05069644	1.53
1	6	1.0	1.0	40											30.0							B381387	196.60	198.12	0.009			VA05069644	1.52
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-297C

PROJECT: Dublin Gulch - 1735

ELEVATION: 996 m

BEARING: 000 | DIP: -60°

DATE STARTED: 21-Jul-05 | DATE COMPLETED: 25-Jul-05

LOGGED BY: Melodie Stone & Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459608 NORTHING: 7099297

COORD SYSTEM: NAD 83: EASTING: 459489 NORTHING: 7099481

NAD 27 (CORRECTED for historic grid): EASTING: 459578 NORTHING: 7099307

SECTION LINE(historic grid): 459575 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 16.5m

Deviation:

Casing: 16.5m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B382618 - B382680

Requisition #: MASP448STRGOL.05Q Date Shipped: 5-Aug-05

Lab Record #: VA05066355 Date Received: 11-Aug-05

Sample Sequence: B382681 - B382700, B363201 - B363323

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05067826 Date Received: 12-Aug-05

Duplicates:	382622; 382642; 382662; 382682; 383202; 383222; 383242; 383262; 383282; 383302; 383322
Preparation Duplicate/ Check Assay:	382629; 382649; 382669; 382689; 383209; 383229; 383249; 383269; 383289; 383309
Standards:	382630; 382650; 382670; 382690; 383210; 383230; 383250; 383270; 383290; 383310
Blanks:	382636; 382656; 382676; 382696; 383216; 383236; 383256; 383276; 383296; 383316

FROM	TO	LITHOLOGY
16.50	82.10	MSED
82.10	119.54	HFLS
119.54	161.00	GND
161.00	161.17	pebbles, variable lithologies
161.17	265.18	GND

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	338.2	-61.6	004.2	005.2
134.11	342.0	-62.9	008.0	009.0
201.17	335.0	-48.3	001.0	002.0
265.18	335.0	-48.3	001.0	002.0
	SUSPECT SURVEYS			

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 1 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-16.50	0.00	16.50	Casing - No recovery						
80	16.50-82.10	16.50	35.05	Highly oxidized to crumbly gravel and sand texture. Competent rocks with visible laminations are in chunks up to 10cm long. From 16.50 to 24.20m rock is dominated by yellowish brown clay to crumbly angular gravel. From 24.20 to 34.80m texture is course sand to angular cobbles and the colour is dark grey with dark brown limonite on all broken faces. There is a 25cm zone of yellowish brown from 34.80 to 35.05m. No qtzite or veins in section so no samples. Foliation is not visible over much of section; Where it is: @21.00m: 10°, @22.45m: 20° - 160° (folded), @24.80m: 20°, @28.60m: 30°, x-cutting qtz/carb veinlet at 120°, @31.90m: 5°, x-cutting carb vn to 120°, @33.00m: 10°.	4			2		
80		35.05	42.30	More competent but still heavily oxidized MSED. Aphanitic texture and mineralogically separated between mafic, felsic and pure qtz laminations. Foliation measurements: from 35.05 35.35m: 105-120°, @36.65m: 60°, @38.50m: 125°, @39.90m: 40-65°, and @42.10m: 40°. Speckled oxidation product of iron within qtz vns (up to 15%) could be hematite or old magnetite (1-2mm grains). "Vein" from 40.27-40.57m has saccharine texture; looks like qtizite but is deemed a vn as it has similar angles as nearby vns x-cutting foliation.	4			1	1	
80		42.30	51.05	MSED: Crumbly coarse sand (75%) to 10cm lengths of core (25%); MSED is zoned (~2m) to mafic-rich and felsic rich sections; All with fine foliation still visible; Qtz veins still crosscut foliation. Foliation: At 42.35m = 45°; @44.6m = 50°; @46.4m = 50°; @47.7m = 30°; @49.0m = 15°; @50.5m = 30° TCA.	3			2	1	
80		51.05	58.64	MSED: Mineralogically separated MSED into wide zones of laminated mafics and pure qtz approx 40cm wide on avg; 10cm yellow clay-rich zone at 57.2m; Gravel clay from 57.5-57.91m; Carb in irregular veinlets; Stained with limonite; Foliation: At 51.3m = 25° TCA; @52.25m = 30° TCA; @53.9m = 25° TCA; @55.6m = 50° TCA; @56.45m = 45° TCA; @58.0m = 30° TCA; Various Indicators of extension and compression: at 51.72m a qtz bleb appears to be old vein compressed to interact with and re-route foliation in MSED, or could be compressed post-separation in MSED; other zones have feldspars concentrated at the edges of pure quartz as well. These are not considered veins here; "Veins" are typically associated with calcite-siderite (limonite) and have selvages.	2			2	2	
80		58.64	64.68	MSED: Predominant color is medium to light brown, from intense oxidation of iron-rich rock. Non-oxidized zones include more felsic minerals and quartz layers. Porphyroblastic texture stands out against laminated, oxidized sections. Porphyroblasts possibly andalusite (tabular aggregates). First appearance of hornfels at 60.50-60.70m. Foliations: @58.8m = 40° TCA; @60.60m = 55° TCA; @62.00m = 30-50° TCA; @63.4m = 50° TCA; @64.3m = 55° TCA.	4	1		2	2	
80		64.68	74.17	MSED: Oxidation, limonite staining and carbonate-infused clays are greatly reduced; Rock is Biot-Hornfelsed. Veins and irregular blebs of qtz with minor carbonate still appear, are generally roughly parallel to foliation or are within it, with augen texture. Some veins crosscut the foliation and are noted here. Between 65.53m - 67.06m no veins appear. Qtz blebs (>4cm in diameter) have offshoots of qtz parallel to and at a complementary angle (90° TCA) to foliation, eventually pinching out. Foliations: @ 64.68m = 50°; @66.0m = 50°; @67.2m = 50°; @68.45m = 45°; @70.0m = 50°; @71.0m = 45°; @72.6m = 45°; @73.85m = 45° TCA.	2	2		1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																			
						Selvages				Sulphides									Oxidation					Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	3	0.2	0.2	60		0.5	q	5	5													B382618	27.43	28.46	**0.024**			VA05066355	1.03
1	3	0.4	0.4	60		0.0																B382619	30.48	32.00	**0.006**			VA05066355	1.52
2	1	1.0	2.0	5		2.0	q	2	5	tr								5.0				B382620	35.05	36.58	**0.053**			VA05066355	1.53
3	1	6.0	13	50		0.0				tr								5.0				B382621	36.58	38.10	**0.148**			VA05066355	1.52
3	1	6.0	13	50		0.0				tr								5.0				B382622	36.58	38.10	**0.023**	DUP		VA05066355	1.52
3	1	1.5	3.5	30		0.5	q/cb	2	5	2.0								5.0				B382623	38.10	39.62	**0.010**		cuts strong foliation	VA05066355	1.52
3	1	1.5	3.0	45		0.0				10								4.0				B382624	39.62	40.27	**0.025**			VA05066355	0.65
1	1	30	30	20		0.0				4.0								5.0				B382625	40.27	40.57	**0.020**			VA05066355	0.30
0																						B382626	40.57	41.15	**0.031**		possibly selvage from large qtz vein	VA05066355	0.58
2	1	1.0	2.0	5		0.5	q/cb	2	5	5.0								4.0				B382627	41.15	42.30	**4.810**			VA05066355	1.15
2	1	1.0	1.3	130	150	1.0	q	2	4	5.0								5.0				B382628	42.30	43.21	**0.603**			VA05066355	0.91
2	1	1.0	1.3	130	150	1.0	q	2	4	5.0								5.0				B382629	42.30	43.21	**0.169**	PD/CA		VA05066355	0.91
																						B382630	STANDARD 2B		**3.040**	2B		VA05066355	
2	1	4.0	6.0	50		4.0	q	4	2	7.0								5.0				B382631	43.21	44.20	**0.014**			VA05066355	0.99
3	1	1.0	3.0	140		6.0	q	3	2	2.0								5.0				B382632	44.20	45.72	**<0.005**			VA05066355	1.52
3	1	1.0	2.5	140	160	2.0	q	4	3	5.0								5.0				B382633	45.72	47.24	**<0.005**			VA05066355	1.52
																							47.24	48.77					1.53
																							48.77	50.29					1.52
																							50.29	51.05					0.76
3	1	1.0	2.0	130	150	6.0	q	1	4	2.0			0.1					2.0					51.05	51.82					0.77
2	1	0.5	1.0	150		2.0	q/cb	2	4	0.1													51.82	53.34					1.52
1	6	0.5	0.5	130		1.0	q/k/cb	3	5	40.0	0.1							5.0				B382634	53.34	54.16	**<0.005**		ox'd hem 55%	VA05066355	0.82
1	1	50.0	50.0	100		0.0				2.0			0.1					5.0				B382635	54.16	54.86	**<0.005**			VA05066355	0.70
4	1	1.0	3.5	100	165	2.0	q/k/cb	3	4	0.1								5.0					54.86	56.39					1.53
1	1	1.5	1.5	0	140	20.0	cb/q/k	4	4	4.0								5.0					56.39	57.91			cb used same pathway		1.52
1	1	1.0	1.0	140		2.0			5	5.0								5.0					57.91	58.64			with hem		0.73
2	1	4.0	6.0	135	160	2.0	q/cb	2	5	0.1								5.0					58.64	59.44					0.80
2	1	2.0	3.0	130	150	1.0	q/cb	2	5	5.0			0.1					4.0					59.44	60.96					1.52
																						B382636	BLANK		**0.006**			VA05066355	
5	1	2.0	5.5	150	90	0.0				8.0			0.1					4.0				B382637	60.96	62.48	**0.190**		one small vein @ 90°	VA05066355	1.52
3	1	2.0	4.0	150	140	0.0				3.0								5.0				B382638	62.48	64.01	**0.486**			VA05066355	1.53
2	1	2.5	4.5	150	120					0.1			2.0					5.0					64.01	64.48					0.47
2	1	1.0	2.0	160	135	2.0			5								0.1						64.48	65.53			20° and 55° in one deformed vein. Other vein @ 20°		1.05

DRILL LOG LEGEND - P1	DATE: July 20-26th, 2005	PAGE 3 of 14	
DRILL HOLE # : DG05-297C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		74.17	79.85	MSED: With fine laminations and fat qtz blebs; From 74.17m to 75.83m color is light orange from intense carbonate and limonite throughout qtz-rich zone. Texture crumbly, with quartz pieces ~ 2cm in diameter. Foliations: @74.4m = 35°; @76.0m = 20°; @77.5m = 40°, @79.0m = 40° TCA.	3			1	1	
80		79.85	82.10	Very crumbly MSED covered with limonite to 80.77m, average size of 2cm; From 80.77m-81.70m, more competent but intensely stained yellow and orange (lim and carb); At 81.7-82.1m, competent with few limonite-covered fracture faces. Foliations: @ 80.1m = 50°, @81.9m = 50°, @82.1m = 45° TCA.	3				2	
81	82.10-119.54	82.10	88.39	MSED: Aphanitic HFLS with qtz veins highly rearranged and often parallel to foliation. Their appearance is compacted, rounded blebs, with 'tails' frequently pointing into foliation. HFLS color is dark purplish black. Foliation: @82.5m = 40°, @84.2m = 40°, @85.9m = 40°, @87.55m = 40°.	2				1	
81		88.39	92.96	MSED: HFLS continues; Silicified 'veins' parallel to foliation are less irregular-shaped, more smooth eyes within foliation. Veins crosscutting foliation contain sulphides and have jagged edges, incorporating into foliation. Real aspy associated with veins in this zone. Foliations: @88.6m = 40°, @90m = 60°, @91.5m = 60°, @92.8m = 60°.	2		1		1	
81		92.96	107.80	MSED: Silicified Hornfels, deep purple to greenish purple. Qtz veins (with carbonate) still parallel to and at a high angle to foliation, contain aspy/some scorodite, and moly. QZZ zones (v. silicifed) up to 20cm, wide contain disseminated aspy in tiny (1mm) grains, unaltered. HFLS sections show porphyroblasts of andalusite in random orientations acicular. Foliations: @ 93.5m = 60°; @94.8m = 55°, @96.1m = 40°; @97.6m = 50°; @99.4m = 40°; @101.0m = 40°; @102.2m = 40°; @103.6m = 55°; @104.6m = 35°; @107.0m = 40° TCA.	1				1	
81		107.80	113.53	(MSED) Silicified HFLS; Qtz-rich zone with very minor carbonate and limonite on fracture faces; From 111.25 - 113m is QZZ; Section is 80% qtz, 20% is 1-2mm veinlets of HFLS, biot, chl, ser, cb. These veinlets are derived from pieces of HFLS trapped into intruding qtz from the GND intrusion (just below 119.54m); Foliations: @107.9m = 30°; @109.65m = 40°; @110.90m = 30 - 50°; @112.22m = 35-50°.	1	1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: phl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																							65.53	67.06					1.53
5	1	1.0	4.0	140		2.0	q	2	4	3.0							2.0	5.0				B392639	67.06	68.58	0.018			VA05066355	1.52
1	1	0.4	0.4	145		1.0	q	4	1													B392640	68.58	70.10	0.005			VA05066355	1.52
6	1	1.0	6.0	140	160	2.0			5	5.0							0.1	5.0				B392641	70.10	71.63	0.008			VA05066355	1.53
6	1	1.0	6.0	140	160	2.0			5	5.0							0.1	5.0				B392642	70.10	71.63	0.008	DUP		VA05066355	1.53
1	4	0.3	0.3	150		0.0				0.0													71.63	73.15					1.52
																							73.15	74.17					1.02
1	1	2.0	2.0	100																			74.17	75.83					1.66
2	1	5.0	9.0	140		0.0				0.1								5.0					75.83	76.85					1.02
2	1	1.0	2.0	140																			76.85	77.72					0.87
3	3	0.5	1.3	140	150	0.5	q/cb	2	4	1.0								5.0					77.72	79.25					1.53
3	1	10.0	20.0	50		0.0																							
2	1	1.0	1.2	140		0.5	q/cb	2	3														79.25	79.85					0.60
1	3	0.5	0.5	140		1.0	q/cb	3	1														79.85	80.77					0.92
1	1	3.0	3.0	80																			80.77	82.10					1.33
5	1	2.0	7.5	140	140	1.0	cb/q	2	3	0.1								5.0				B382643	82.10	83.34	0.147			VA05066355	1.24
4	1	4.0	8.0	130	15	2.0	cb/q	3		0.1			0.1					4.0	4.0			B382644	83.34	84.20	0.014		selvage appears perpendicular to foliation, but not parallel	VA05066355	0.86
3	1	15.0	32.0	50		4.0	q/cb	3	2				5.0						4.0			B382645	84.20	85.34	0.040			VA05066355	1.14
1	3	1.0	1.0	145		0.0				1.0								5.0											
2	1	3.0	6.0	140	30	8.0	q/cb	4	2	3.0								5.0				B382646	85.34	86.20	0.006			VA05066355	0.86
2	1	20.0	25.0	40		4.0	q/cb	2	2				5.0						4.0			B382647	86.20	86.87	0.022			VA05066355	0.67
3	1	6.0	9.0	150		6.0	q/cb	4	2	3.0												B382648	86.87	87.61	0.066			VA05066355	0.74
																						B382649	86.87	87.61	0.065	PD/CA		VA05066355	0.74
																						B382650	STANDARD 4D		0.420	4D		VA05066355	
4	1	3.0	10.0	125	45	1.0	q/cb	2	1													B382651	87.61	88.39	0.044			VA05066355	0.78
3	1	2.0	6.0	150		2.0	q/cb	1	3													B382652	88.39	89.92	0.019			VA05066355	1.53
4	3	3.0	5.0	50	35	1.0	q/cb	2		1.0								5.0											
4	1	4.0	7.0	40	125	3.0	q/cb	4	3				5.0						0.0			B382653	89.92	91.44	0.238			VA05066355	1.52
2	3	1.0	1.5	50		1.0	q/cb	3	1																				
4	1	1.0	4.0	60	120					2.0			2.0					5.0	5.0			B382654	91.44	92.96	0.115			VA05066355	1.52
4	3	0.5	1.8	155									15.0						0.0										
4	1	1.5	5.0	30	50	2.0	q/cb	3	3	0.1			10.0					2.0	3.0			B382655	92.96	94.49	0.084			VA05066355	1.53
																						B382656	BLANK		<0.005			VA05066355	
4	1	2.0	5.5	160	135	1.0	q/cb	3	1				5.0						2.0			B382657	94.49	96.01	0.120			VA05066355	1.52
4	1	2.0	8.0	150	45	2.0	q/cb	3	2				3.0				0.1					B382658	96.01	97.54	0.011			VA05066355	1.53
7	1	6.0	15.0	60	150	2.0	q/cb	1	3		3.0		2.0					1.0	5.0			B382659	97.54	99.06	<0.005		selvage on veins to 150°	VA05066355	1.52
5	1	1.0	4.0	60	140					1.0			2.0						5.0			B382660	99.06	100.58	<0.005			VA05066355	1.52
3	1	1.5	4.0	145		2.0	q/cb	1	1				1.0				1.0					B382661	100.58	102.11	0.014			VA05066355	1.53
3	1	1.5	4.0	145		2.0	q/cb	1	1				1.0				1.0					B382662	100.58	102.11	0.005	DUP		VA05066355	1.53
2	1	1.5	2.5	50	140	0.0				1.0								5.0				B382663	102.11	103.63	<0.005			VA05066355	1.52
6	1	20.0	30.0	40	130	1.0	q/cb	3	1													B382664	103.63	105.16	<0.005			VA05066355	1.53
10	1	8.0	25.0	40	160	1.0	q/p	4	1	1.0			4.0					5.0	0.0			B382665	105.16	106.68	0.006		p=pyroxene	VA05066355	1.52
2	1	0.4	0.7	135	35	0.0				1.0								5.0				B382666	106.68	107.80	<0.005			VA05066355	1.12
4	1	1.0	4.0	40																		B382667	107.80	108.90	<0.005		ox'd py, not po	VA05066355	1.10

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 5 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81		113.53	119.54	MSED: Last section of MSED's contact wi GND at 119.54m; HFLS more effected by carbonate, somewhat broken up, still 70% competent core or angular cobbles, 30% carb-clay and HFLS-Clay (dark purple, flaky to crumbly and soft).		1		1	2	
10	119.54-161.00	119.54	136.28	GND: As MSED/HFLS acted as a caprock to carbonate intrusion, calcite is concentrated in this uppermost section of GND. It is more permeable than HFLS as well. Carbonate seen in veinlets, veins and throughout GND matrix (btwn qtz, biot, plag, etc.), causing it to be crumbly and soft and carb-clay rich. Nothing competent until 126.49m where core lengths are up to 15cm. One length of 20cm at 134.92m. 22cm wide zone of dark grey clay at 129.4 - 129.62m contains ox'd py? All sericite/carbonate altered.						
10		136.28	143.26	GND: Section is 90% alt'd with carb and chlorite throughout the matrix of GND, such that the color is greenish-brown-grey. At 142.60m, a qtz/carb vein contains large spahlerite and chalcopyrite in up to 1cm irregular to subhedral bands. Oxidation noted is predominantly within sulphides-pyrite.	1	1	2		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	0.5	3.0	150						3.0	2.0							5.0				B382668	108.90	109.73	0.009			VA05066355	0.83
																						B382669	108.90	109.73	0.009	PD/CA		VA05066355	0.83
6	1	1.5	4.5	15	35	1.0	q	4	0								5.0					B382670	STANDARD 5E		1.405	5E		VA05066355	
5	1	6.0	9.0	40		1.0	q	2	0								0.1					B382671	109.73	111.25	<0.005			VA05066355	1.52
2	3	0.5	1.0	150		0.0				0.0												B382672	111.25	112.22	0.039			VA05066355	0.97
3	3	0.5	1.5	150		0.0																B382673	112.22	112.78	<0.005			VA05066355	0.56
5	1	0.5	2.5	125		0.0					1.0		3.0						5.0		2.0	B382674	112.78	113.53	<0.005			VA05066355	0.75
3	1	5.0	8.0	153		2.0	chl/ser	3	1		2.0		5.0						5.0			B382675	113.53	114.60	<0.005		no aspy visible, only scor	VA05066355	1.07
																						B382676	BLANK		<0.005		branching veins, no selvage	VA05066355	
7	1	8.0	18.0	160	120	0.0							7.0						5.0			B382677	114.60	115.72	<0.005			VA05066355	1.12
4	1	2.0	6.0	140									5.0						4.0			B382678	115.72	116.02	<0.005			VA05066355	0.30
9	1	1.0	9.0	130		0.0					1.0								2.0			B382679	116.02	117.35	<0.005			VA05066355	1.33
4	3	2.0	3.0	40									3.0						0.0			B382680	117.35	118.87	<0.005			VA05066355	1.52
4	1	4.0	8.0	40	155	1.0	cb	1	0				0.1									B382681	118.87	119.54	0.006			VA05067826	0.67
4	1	4.0	8.0	40	155	1.0	cb	1	0				0.1									B382682	118.87	119.54	0.006	DUP		VA05067826	0.67
0																						B382683	119.54	120.40	0.094			VA05067826	0.86
2	3	1.0	2.0							0.1												B382684	120.40	121.92	0.295		pieces/ crumbly	VA05067826	1.52
2	1	6.0	7.0	50	40	14.0	q/cb/chl	3		5.0			5.0					5.0				B382685	121.92	123.44	13.450		clean' aspy, ox'd py in 1mm lenses	VA05067826	1.52
3	3	3.0	9.0	40	60	10.0	cb	4	0				0.1						5.0			B382686	123.44	124.97	0.119			VA05067826	1.53
3	3	4.0	7.5	35	130	10.0	cb/cbl	4		5.0								5.0				B382687	124.97	126.49	0.293			VA05067826	1.52
2	1	1.0	2.0	40	15	2.0	q/chl	3	0	2.0			0.1					4.0				B382688	126.49	128.02	0.709			VA05067826	1.53
3	4	0.5	1.5	75																									
2	1	1.0	2.0	40	15	2.0	q/chl	3	0	2.0			0.1					4.0				B382689	126.49	128.02	1.165	PD/CA		VA05067826	1.53
3	4	0.5	1.5	75																									
																						B382690	STANDARD 6F		1.110	6F		VA05067826	
4	1	1.5	4.0	60		2.0	q/cb	3	1	5.0								5.0				B382691	128.02	129.54	0.560			VA05067826	1.52
1	1	1.5	1.5	20		2.0	q/cb	2	0													B382692	129.54	131.06	0.048			VA05067826	1.52
3	1	1.0	3.0	85	135	0.0				0.1								5.0				B382693	131.06	132.59	0.852			VA05067826	1.53
3	1	0.5	1.5	145		0.5	q/cb	3			10.0							3.0				B382694	132.59	134.11	0.055			VA05067826	1.52
1	3	1.0	1.0	70		2.0	q/cb	2		1.0								5.0				B382695	134.11	134.91	0.117			VA05067826	0.80
																						B382696	BLANK		<0.005			VA05067826	
6	1	2.0	6.0	20	55	1.0	q/cb	3	0		6.0		1.0									B382697	134.91	136.28	0.891			VA05067826	1.37
3	1	5.0	9.0	20	50	10.0	q/cb/chl	4		10.0	4.0		2.0					1.0				B382698	136.28	137.16	0.325			VA05067826	0.88
1	3	0.4	0.4	30		2.0	q/cb	4		4.0								5.0											
2	1	3.0	6.0	30	10	6.0	q/cb/chl	4		10.0								2.0				B382699	137.16	138.00	0.540			VA05067826	0.84
5	6	1.0	3.5	40		10.0	q	2		70.0	10.0		10.0					2.0											
1	1	4.0	4.0	50		10.0	q/cb/chl	4		10.0			2.0		4.0			2.0				B382700	138.00	138.68	0.167		sulphides conc at margins	VA05067826	0.68
2	4	0.4	0.8	35		3.0	cb	2		20.0								4.0											
1	1	4.0	4.0	50		60.0	cb/chl	4		8.0	10.0		1.0					3.0				B363201	138.68	140.21	0.794		sulph vein w/in qtz vein selvage	VA05067826	1.53
1	6	0.5	0.5	35						80.0								3.0											
1	4	0.5	0.5	40		30.0	cb/chl	4		10.0					1.0			4.0											
1	1	4.0	4.0	50		60.0	cb/chl	4		8.0	10.0		1.0					3.0				B363202	138.68	140.21	0.574	DUP		VA05067826	1.53
1	6	0.5	0.5	35						80.0								3.0											
1	4	0.5	0.5	40		30.0	cb/chl	4		10.0					1.0			4.0											
4	4	0.3	1.2	40	30	20.0	cb/chl	4		5.0								5.0				B363203	140.21	141.73	0.058			VA05067826	1.52
2	6	0.2	0.4	20		20.0	q/cb	4		60.0								5.0											
2	1	1.5	2.5	35	60	80.0	cb/chl	4		15.0	2.0							1.0				B363204	141.73	142.55	0.444			VA05067826	0.82
3	1	2.0	4.5	4		20.0				10.0	5.0							2.0				B363205	142.55	143.26	3.600			VA05067826	0.71
1	3	0.5	1.5	5								8.0			15.0														

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 1 of 14	
DRILL HOLE # : DG05-297C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		143.26	148.88	GND: Moderate carbonate and chlorite alteration around veinlets of carbonate and few quartz veins; Generally unaltered GND: One 1cm zone of medium-grey clay at 143.46m; Carb-rich clay; Another 10cm wide at 146.17m		1	2	1	2	
10		148.88	150.88	GND: Unaltered; A few small quartz veins with very minor carbonate, pyrrhotite					1	
10		150.88	161.00	GND: Moderate carbonate intrusion into 80% unaltered GND: Zones of shear/re-arrangement/sulphide-clay						
-1	161.00-161.17	161.00	161.17	Random sub-rounded pebbles, lithology includes argillite, qtzite, granite and granodiorite; Max pebble size 4 cm in diameter.						
10	161.17-265.18	161.17	162.04	GND: Mostly unaltered; 6cm section of moderate sericite alteration; Short (~10cm) section of highly fractured GND with carbonate and sericite on fracture faces.		3			1	
10		162.04	163.07	GND: At 162.25 - 162.59m = Moderate chlorite alteration; At 162.59 - 163m = Moderate sericite alteration. Unaltered GND + chl altered at contact at ~30° TCA; Gradual contact with chlorite and sericite altered GND.		3	4			
10		163.07	164.59	GND: From 163.07 to 164.59m = Moderate to intense chlorite alteration; Gradual contact into unaltered GND; Multiple carbonate veins; Extremely fractured from 164.54 - 164.59m.			4			
10		164.59	166.12	GND: Mostly unaltered GND: Multiple <2mm oxidized sulphide veins; Disseminated pyrite on fractures with slickenlines.						
		166.12	167.64	GND: Compositionally unaltered; Pyrite smeared along slicken-slides						
		167.64	168.18	Appears brecciated with oxidized sulphide veining (?). Main zone contained by sharp oxidized sulphide veins at ~45° TCA; Only minor veining outside zone grading back into GND.	4				5	
10		168.18	175.10	GND: Unaltered; minor sulphides (mostly po and py); Slip faces at 60° TCA (Carbonate faces); Multiple carbonate, quartz and sulphide veinlets.						
10		175.10	175.26	GND: Highly fractured; Fracture faces have chl slickenlines with minor diss py; Po veinlets with quartz selvages parallel to fractures.						
10		175.26	181.36	GND: With very abundant carbonate veining; At 179 - 181m = Carbonate veining takes on pink color; At 176.78 - 177.05m = Altered carbonate fault gouge with ~ 4mm oxidized sulphide vein with quartz selvage (1cm) in center of gouge and parallel to contact (At 60° TCA); GND has a darker grey appearance; Many fracture faces have slickenlines in contact with minor pyrite smearing (Slickenlines are randomly oriented).			1		3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, oo = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	1.0	3.0	40		3.0	q/chl	3	0		5.0	2.0						3.0				B363206	143.26	144.78	**0.513**		10% py in one vein only	VA05067826	1.52
2	3	3.0	5.0	30	20	2.0	cb/chl	4	0	10.0	7.0	5.0	1.0						4.0										
3	1	3.0	6.0	40	30	2.0	q/chl	2	0		5.0	7.0										B363207	144.78	146.30	**0.112**			VA05067826	1.52
1	3	3.0	3.0	25		4.0	q/cb	3	1	20.0	4.0		2.0																
1	1	1.0	1.0	25		10.0	cb/chl	4	0	5.0	0.1							4.0				B363208	146.30	147.83	**0.030**		silicified zone around carb veins (not selvage)	VA05067826	1.53
5	4	0.5	1.0	10	35	0.0																							
1	1	1.0	1.0	25		10.0	cb/chl	4	0	5.0	0.1							4.0				B363209	146.30	147.83	**0.032**	PD/CA		VA05067826	1.53
5	4	0.5	1.0	10	35	0.0																							
																						B363210	STANDARD 2B		**2.690**	2B		VA05067826	
4	1	3.0	7.0	30		2.0	q/chl	3	0		10.0		3.0									B363211	147.83	148.88	**2.620**			VA05067826	1.05
4	1	1.0	3.0	40		1.0	q/cb	2			0.1							1.0				B363212	148.88	150.35	**0.090**			VA05067826	1.47
0																						B363213	150.35	150.88	**0.013**			VA05067826	0.53
3	1	1.0	2.0	35		1.0	q	3	0		5.0											B363214	150.88	152.40	**0.075**			VA05067826	1.52
0																						B363215	152.40	153.92	**0.012**			VA05067826	1.52
																						B363216	BLANK		**<0.005**			VA05067826	
5	6	0.3	2.1	60						100.0								5.0				B363217	153.92	155.45	**0.037**		wispy	VA05067826	1.53
4	1	1.5	3.5	25	65	2.0	q	2		2.0	5.0		5.0						3.0			B363218	155.45	156.97	**0.108**			VA05067826	1.52
2	1	2.0	3.0			1.0	q	3			5.0											B363219	156.97	158.50	**0.030**			VA05067826	1.53
2	4	0.5	0.9	70		0.5	cb	3																					
3	4	0.2	0.6	70		1.0	cb	3														B363220	158.50	160.02	**0.027**			VA05067826	1.52
4	1	1.0	4.0	30		1.0	q	4			2.0		0.1									B363221	160.02	161.00	**0.016**			VA05067826	0.98
4	1	1.0	4.0	30		1.0	q	4			2.0		0.1									B363222	160.02	161.00	**0.077**	DUP		VA05067826	0.98
																							161.00	161.17					0.17
6	3	1.0	2.5	30	60	1.0	q/s/cb	1			1.0		0.1		0.1							B363223	161.17	162.04	**0.042**			VA05067826	0.87
4	1	1.0	2.0	30							5.0		0.1									B363224	162.04	163.07	**0.024**		po only in one vein	VA05067826	1.03
9	1	1.5	3.5	30	150	1.5	q/s/cb	5		2.0	2.0		0.1					1.0				B363225	163.07	164.59	**0.076**		ox'd py in qtz vein	VA05067826	1.52
9	5	1.0	5.0	30	45	2.5	s/q	4		0.1	1.0							1.0				B363226	164.59	166.12	**0.200**			VA05067826	1.53
2	4	0.2	0.4	30	10	0.5	cb	4	0	3.0	9.0							2.0				B363227	166.12	167.64	**0.261**			VA05067826	1.52
2	6	0.5	1.0	60			q/s/cb	4	3	3.0								4.0				B363228	167.64	168.18	**0.891**			VA05067826	0.54
																						B363229	167.64	168.18	**0.992**	PD/CA		VA05067826	0.54
																						B363230	STANDARD 5E		**1.340**	5E		VA05067826	
2	1	0.3	0.5	30						0.1	0.1							1.0				B363231	168.18	169.16	**0.308**			VA05067826	0.98
6	1	0.3	1.0	30		0.8	q	4		0.1	1.0							1.0				B363232	169.16	170.69	**0.037**			VA05067826	1.53
3	1	0.5	0.8	30						0.1	0.1	0.1										B363233	170.69	172.21	**0.079**			VA05067826	1.52
6	1	1.0	3.0	45	30	0.5	q	3	0	2.0	3.0	0.1	0.1									B363234	172.21	173.74	**0.636**			VA05067826	1.53
							chl																						
8	1	0.8	30.0	30	60	3.0	q	4	0	0.1	5.0	0.1						1.0				B363235	173.74	175.26	**1.760**			VA05067826	1.52
	4						chl	3																					
																						B363236	BLANK		**0.005**			VA05067826	
3	4	3.0	4.0	30	10																	B363237	175.26	176.07	**0.016**			VA05067826	0.81
6	4	0.6	2.0	60		0.5	cb	2	0	0.1	3.0	0.1	0.1									B363238	176.07	176.78	**0.063**			VA05067826	0.71
6	1	1.0	3.0	40	60	0.1	cb	3		0.1	0.1		1.0						2.0			B363239	176.78	178.31	**0.076**			VA05067826	1.53
	4																												
3	6	0.5	1.6	45						50.0								3.0				B363240	178.31	179.83	**0.404**			VA05067826	1.52
	1	1.0								2.0																			
	4	0.3									1.0																		
4	1	1.0	3.0	30		0.5	q			0.1	1.0											B363241	179.83	181.36	**0.078**			VA05067826	1.53
	4	0.3																											
4	1	1.0	3.0	30		0.5	q			0.1	1.0											B363242	179.83	181.36	**0.076**	DUP		VA05067826	1.53

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 9 of 14	
DRILL HOLE # : DG05-297C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		181.36	183.33	GND: Extremely carbonate altered GND (fault gouge?); Locally in contact with less altered GND parallel to core axis; Sharp contact with dark green, softer GND (CHL altered) at ~30° TCA.					5	
10		183.33	198.12	GND: Near parallel to core axis between chlorite altered GND and intensive carbonate alt'd GND; Core changes between the two; Local intense clay and carbonate alteration; At 196.45m = 4 parallel quartz veins of chlorite and quartz with minor (~1%) pyrrhotite.			3		3	
10		198.12	206.27	GND: Mostly unaltered GND; Thin <2mm veins of carbonate still dominant but are less than previous; Two locations of intensely altered (carb) fault breccia (displaced veins within breccia) with sharp contacts between 40-60° TCA; Slickenline on 20° face at 60° TCA.						
10		206.70	219.00	GND: Predominantly unaltered GND; with local zones of slight chlorite alteration; Very minor carbonate veinlets (Except 1cm carb vein at 10°); Quartz veining is dominantly with chlorite or sericite (?) alteration; Slip faces have chlorite +/- carbonate; 10° face + 30° slickenlines; 30° face with 70° slickenlines; 45° with 80° slickenlines.			2			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
	4	0.3																											
2	1	1.0	1.3	30																		B363243	181.36	181.91	**0.053**			VA05067826	0.55
	4	0.3		90																									
1	4	1.0	1.0	60																		B363244	181.91	183.33	**0.163**			VA05067826	1.42
2	1	2.0	3.0	60																		B363245	183.33	184.40	**0.221**			VA05067826	1.07
3	1	3.0	6.0	40						1.0	5.0	0.1						1.0				B363246	184.40	185.93	**0.156**			VA05067826	1.53
2	1	1.5	2.0	60		0.5	q	5			3.0							1.0				B363247	185.93	187.45	**0.067**			VA05067826	1.52
3	1	1.5	2.2	30		0.5	q	3			1.0											B363248	187.45	188.98	**0.024**			VA05067826	1.53
	4	0.3	0.3	90																									
3	1	1.5	2.2	30		0.5	q	3			1.0											B363249	187.45	188.98	**0.043**	PD/CA		VA05067826	1.53
	4	0.3	0.3	90																									
																						B363250	STANDARD 6F		**2.810**	6F		VA05067826	
3	1	1.0	2.5	30						0.1								1.0				B363251	188.98	190.50	**0.060**		aspy in only one vein	VA05067826	1.52
2	1	1.0	2.0	30	60					1.0	0.1	0.1						1.0				B363252	190.50	191.32	**0.067**			VA05067826	0.82
1	6	1.5	1.5	40						0.1								3.0				B363253	191.32	192.58	**0.058**			VA05067826	1.26
0																						B363254	192.58	193.23	**0.026**			VA05067826	0.65
1	3	0.3	..3	30		0.5	q	3		3.0	1.0							1.0				B363255	193.23	193.78	**0.022**			VA05067826	0.55
																						B363256	BLANK		**<0.005**			VA05067826	
5	1	1.5	5.5	30	45	0.4	q	3		0.1	1.0							1.0				B363257	193.78	195.07	**0.040**			VA05067826	1.29
	5																												
	3																												
6	1	1.0	4.0	30	150	0.4	q	4			1.0							1.0				B363258	195.07	196.60	**0.027**			VA05067826	1.53
	4																												
2	1	0.5	1.0	30																		B363259	196.60	198.12	**0.017**			VA05067826	1.52
	4																												
9	1	2.0	7.5	30	45	0.5	q	4	0	0.1	2.0							1.0				B363260	198.12	199.64	**0.063**			VA05067826	1.52
	1																												
	6																												
6	1	2.5	6.0	45	30	3.0	q	5			2.0		0.1					1.0				B363261	199.64	201.17	**0.065**			VA05067826	1.53
	6																												
	5																												
6	1	2.5	6.0	45	30	3.0	q	5			2.0		0.1					1.0				B363262	199.64	201.17	**0.283**	DUP		VA05067826	1.53
4	6	1.0	2.5	45		2.0	q	4			2.0							1.0				B363263	201.17	202.69	**0.032**			VA05067826	1.52
	1																												
	3																												
2	1	1.5	2.5	30	45																	B363264	202.69	204.22	**0.069**			VA05067826	1.53
3	1	1.0	2.5	30	45	0.5	q	4			2.0							1.0				B363265	204.22	205.08	**0.041**			VA05067826	0.86
	6																												
8	1	1.0	7.0	45	30	0.3	q	4			2.0		0.1					1.0				B363266	205.08	206.27	**0.097**			VA05067826	1.19
8	1	1.0	3.5	45	30	1.0	q	2			3.0		1.0					1.0				B363267	206.27	207.26	**0.092**			VA05067826	0.99
	6																												
	3																												
	5																												
6	1	1.0	4.0	30	45	0.5	q	3			3.0											B363268	207.26	208.79	**0.052**			VA05067826	1.53
6	1	1.0	4.0	30	45	0.5	q	3			3.0											B363269	207.26	208.79	**0.049**	PD/CA		VA05067826	1.53
																						B363270	STANDARD 6F		**2.800**	6F		VA05067826	
3	1	1.5	2.8	30	0	0.5	q	2			3.0							1.0				B363271	208.79	210.31	**1.580**			VA05067826	1.52
	4						chl																						
4	1	2.0	3.5	30		0.5	q	3			3.0		1.0					1.0				B363272	210.31	211.84	**1.130**			VA05067826	1.53
	6						chl																						
7	1	2.0	5.0	30		0.5	q	3			3.0		0.1					1.0				B363273	211.84	213.36	**0.057**			VA05067826	1.52
	5						chl																						
4	1	1.0	4.0	30							2.0											B363274	213.36	214.88	**0.087**			VA05067826	1.52
5	1	1.5	3.5	30		1.0	q	4			10.0	1.0						1.0				B363275	214.88	216.41	**0.163**			VA05067826	1.53
	6						chl																						

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 11 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		219.00	222.50	GND: Intensely altered GND (sericite); Core is stained green and softer than unaltered GND; Unaltered/Altered ctc runs near parallel to core in places; Contact is moderately gradual; Abundant disseminated blebs of very fine grained pyrite (20%) within 2-3cm of contact with unaltered GND.		3				
10		222.50	236.42	Core alternates between unaltered and sericite altered GND (unaltered GND is more abundant); Contact w/ GND is shallow (0-20°); Secondary altered GND contains disseminated blebs of very fine grained py near the contact; Minor local chlorite altered GND at 228.6 - 228.68m with 10% very fine grained blebs of pyrite; Between 235.15 - 235.87m area of sericite alteration with carbonate alteration as well; Within zone is a 0.5cm pyrite vein at 30° with slickenlines at 60° TCA.		2				
10		236.42	237.15	GND: Intensely altered GND (mostly carbonate alteration with more sericite alteration - greenish hue); Very soft - possibly fault breccia; Thick (1.5cm) quartz veins are cross cut.				2	3	
10		237.15	242.16	GND: Return to alternating unaltered GND and sericite altered GND; Pyrite veins (0.05 - 0.5cm) are common in sericite altered GND; Pyrite associated with carbonate veinlets and qtz veins and disseminated on and around slip faces; Slip faces have chlorite; 20° face with 80° slickenlines; 60° face with 90° slicks; Qtz vein offset (dextral) by carbonate filled fracture.		1				
10		242.16	248.94	GND: Intense sericite alteration with local carbonate alteration; Local intensive sulphide veining and fracturing; Abundant pyrite veining (some offset by carbonate filled fractures) at shallow angles (0-30° TCA); Chloritic slip faces at 5-30° with lines at 60-80°; Sulphide/carbonate vein offset (sinistral) by 5cm.		3			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B363276	BLANK		<0.005			VA05067826	
6	1	0.5	3.0	30	60	1.0	q	4			5.0											B363277	216.41	217.93	0.044			VA05067826	1.52
	6						chl																						
3	1	1.5	2.0	45		0.8	chl	3		1.0	2.0											B363278	217.93	219.00	0.154			VA05067826	1.07
6	1	3.0	6.5	30	45					1.0	5.0							1.0				B363279	219.00	220.40	0.081			VA05067826	1.40
	5																												
	6																												
3	1	1.0	2.0	30		0.2	chl	2		1.0	1.0							1.0				B363280	220.40	221.38	0.026			VA05067826	0.98
2	1	0.4	1.0	30						2.0	1.0											B363281	221.38	222.50	0.152			VA05067826	1.12
2	1	0.4	1.0	30						2.0	1.0											B363282	221.38	222.50	0.031	DUP		VA05067826	1.12
4	1	1.0	3.0	30	10	0.5	chl	3			1.0											B363283	222.50	224.03	0.033			VA05067826	1.53
	3																												
	4																												
2	1	1.0	1.5	30							2.0											B363284	224.03	225.46	0.028			VA05067826	1.43
2	1	2.0	3.0	30						0.1	2.0							1.0				B363285	225.46	227.08	0.135			VA05067826	1.62
																						Missing							
3	1	2.0	4.0	45	30					0.1	2.0											B363287	227.08	228.60	0.092			VA05067826	1.52
	5																												
3	1	2.0	4.0	45	30					0.1	2.0											B363288	228.60	230.12	0.128			VA05067826	1.52
																						B363289	228.60	230.12	0.185	PD/CA		VA05067826	1.52
																						B363290	STANDARD 2B		2.980	2B		VA05067826	
3	1	1.0	3.0	30							1.0											B363291	230.12	231.65	0.020			VA05067826	1.53
4	1	2.0	3.0	30							2.0											B363292	231.65	233.17	0.117			VA05067826	1.52
8	1	1.5	6.5	30		1.0	q	4		0.1	2.0											B363293	233.17	234.70	0.474			VA05067826	1.53
	6																												
3	1	0.6	1.5	30		1.0	q	4			1.0							1.0				B363294	234.70	235.15	0.253			VA05067826	0.45
5	1	1.0	4.0	30		1.0	q	4			1.0											B363295	235.15	236.42	0.155			VA05067826	1.27
	6																												
																						B363296	BLANK		<0.005			VA05067826	
2	1	1.5	2.5	45																		B363297	236.42	237.15	0.165			VA05067826	0.73
3	1	1.0	2.5	45							1.0											B363298	237.15	237.82	0.440			VA05067826	0.67
3	1	0.6	1.5	30	60					1.0	2.0							1.0				B363299	237.82	238.85	0.116			VA05067826	1.03
	6																												
3	1	1.0	2.5	45	30	0.5	q	3			1.0							1.0				B363300	238.85	240.33	0.137			VA05067826	1.48
3	1	0.5	1.0	60	30	1.0	q/cb	3			0.1							1.0				B363301	240.33	241.12	0.105			VA05067826	0.79
	3						s																						
3	1	0.5	1.0	60	30	1.0	q/cb	3			0.1							1.0				B363302	240.33	241.12	0.102	DUP		VA05067826	0.79
	3						s																						
3	1	0.5	1.0	45	30	0.5	q	3		1.0	1.0			1.0				1.0				B363303	241.12	242.16	0.059			VA05067826	1.04
	6						s																						
3	1	1.0	2.0	30		0.5	cb	4		4.0	1.0							5.0				B363304	242.16	243.55	0.058			VA05067826	1.39
	6																												
6	6	1.5	2.0	20						60.0								20.0				B363305	243.55	244.75	0.081			VA05067826	1.20
	1																												
3	4	0.5	1.5	30	60					1.0												B363306	244.75	246.33	0.077			VA05067826	1.58
	6																												
5	6	2.0	3.5	30	45					10.0	1.0							1.0				B363307	246.33	247.72	0.100			VA05067826	1.39
	3																												
2	1	1.0	1.5	45	30																	B363308	247.72	248.94	0.087			VA05067826	1.22
2	1	1.0	1.5	45	30																	B363309	247.72	248.94	0.081	PD/CA		VA05067826	1.22
																						B363310	STANDARD 5E		1.360	5E		VA05067826	

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 13 of 14	
DRILL HOLE # : DG05-297C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION From → To:	From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		248.94	256.18	GND: Mostly relatively unaltered GND with local (20cm) zones of sericite alteration; Disseminated pyrite found in sericite altered zones; From 256.5 - 259.45m = core very fractured; Sericite/Chlorite alteration selvages along fractures and with chlorite on faces.		1	1		1	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides									Oxidation					Interval							
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	1	1.0	2.0	30	45						2.0							1.0				B363311	248.94	249.94	**0.052**			VA05067826	1.00
3	1	1.0	1.5	30	45					2.0	1.0							1.0				B363312	249.94	251.46	**0.071**			VA05067826	1.52
	6																												
3	1	1.0	2.5	30							2.0							1.0				B363313	251.46	252.98	**0.076**			VA05067826	1.52
4	1	1.0	4.0	30	45					0.1	1.0							1.0				B363314	252.98	254.51	**0.100**			VA05067826	1.53
	4																												
2	1	1.0	15.0	30						1.0	1.0											B363315	254.51	256.03	**0.052**			VA05067826	1.52
																						B363316	BLANK		**0.006**			VA05067826	
1	1	0.5	0.5	30							1.0							1.0				B363317	256.03	257.56	**0.056**			VA05067826	1.53
																						B363318	257.56	259.08	**0.057**		Core to fractured	VA05067826	1.52
4	1	1.0	3.5	45							2.0							1.0				B363319	259.08	260.60	**0.119**			VA05067826	1.52
3	1	1.0	2.5	45							2.0							1.0				B363320	260.60	262.13	**0.745**			VA05067826	1.53
4	1	1.0	2.5	45		0.5	q	3			2.0							1.0				B363321	262.13	263.65	**0.149**			VA05067826	1.52
	6																												
4	1	1.0	2.5	45		0.5	q	3			2.0							1.0				B363322	262.13	263.65	**0.197**	DUP		VA05067826	1.52
4	1	1.0	2.5	45	30	2.0	5	3		2.0	1.0							1.0				B363323	263.65	265.18	**0.353**			VA05067826	1.53

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-298C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 891m

BEARING: 000 | DIP: -50°

DATES DRILLING:	DATES LOGGING:
July 21 - 26, 2005	August 7 - 13, 2005

LOGGED BY: Terry Croteau

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459302 NORTHING: 7099379

COORD SYSTEM: NAD 83: EASTING: 459184 NORTHING: 7099563

NAD 27 (CORRECTED for historic grid): EASTING: 459272 NORTHING: 7099389

SECTION LINE(historic grid): 459275 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 0.00 - 8.23m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
8.23	72.25	MSED
72.25	72.82	GND
72.82	95.49	MSED
95.49	95.89	GND
95.89	208.39	MSED
208.39	209.41	GND
209.41	243.36	MSED
243.36	280.42	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B381388 - B381480

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Aug-05

Lab Record #: VA05070460 Date Received: 22-Aug-05

Sample Sequence: B381481 - B381576

Requisition #: MASP448STRGOL.05Q Date Shipped: 19-Aug-05

Lab Record #: VA05072073 Date Received: 25-Aug-05

Duplicates:	381402; 381422; 381442; 381462; 381482; 381502; 381522; 381542; 381562
Preparation Duplicate/ Check Assay:	381389; 381409; 381429; 381449; 381469; 381489; 381509; 381529; 381549; 381569
Standards:	381390 (3C); 381410 (4D); 381430 (2B); 381450 (5E); 381470 (4D); 381490 (3C); 381510 (2B); 381530 (5E); 381550 (6F); 381570 (7G)
Blanks:	381396; 381416; 381436; 381456; 381476; 381496; 381516; 381536; 381556; 381576

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
76.20	343.4	-55.7	9.40	10.40
152.39	347.7	-55.8	13.70	14.70
213.35	349.2	-57.2	15.20	16.20
280.40	351.2	-57.2	17.20	18.20

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 1 of 12		
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 8.23	0.00	8.23	Casing - No Recovery						
80				MSED - Varied composition. Derived from pelitic to arenaceous rocks. May be silicious or phyllitic. Alteration is commonly sericitic, with minor chloritic and argillic present. Foliation is initially at a much lower angle to CA than previous holes.						
80	8.23 - 72.25	8.23	18.29	MSED - Dark grey. Limonite is pervasive and heavily stains fracture faces. Foliation is at low angles to CA. Foliation @ 8.23m -> 10-12°, @9.14m -> 10-15°, @10.67m -> 30-32°, @12.19m -> 40-45°, @13.72m -> 30-32°, @15.24m -> 20-25°, @16.76m -> 0-10°. Recovery is poor. Core is broken into gravel sized pieces (70%) and 5cm or larger (30%). @16.76m, 18cm APL dyke @10° to CA. Fabric appears gneissic and is parallel to CA.	3	2		1	1	
80		18.29	32.73	Silicious MSED - Dark grey to dark blue. Foliation continues to be between 10° and 45° to CA. Lim is less pervasive, but continues on the fracture faces. Foliation @18.29m ->15-20°, @19.81m -> 25-30°, @21.34m -> 25-30°, @22.86m -> 22-25°, @24.38m -> 20-22°, @25.91m -> 20-25°, @27.43m -> 30-35°, @28.96m -> too broken for measurement, @30.48m -> too broken for measurement, @32.00m -> 30-35° - folded. @20.72m - 5cm APL dyke @85° to CA.	2					
80		32.73	36.72	Intense clay alt'n throughout section. Core is soft but coherent. @36.85m - 15cm gouge containing MSED frags - possible hydrothermal alt'n.	2			4	2	
70		36.72	54.86	QZZ - Light grey to grey. Residual foliation @ higher angles to CA (55-60°). Qtz veins increase in number and size, up to 35cm. 95% of the veins are 1-3cm in width. There is also a corresponding increase in sulphides, though less intense. 70% of the sulphides are found on fracture faces and 75% of the aspy has been altered to Scorodite. @50.29m - 9cm grey qtz vein @ 60° to CA @51.82m - 8cm grey qtz vein @ 50° to CA @53.34m - 35cm grey qtz vein @ 40° to CA, 5% scor			2	2	1	
80		54.86	58.63	Silicified MSED - light grey to grey. Lighter coloured qtz ellipsoids are banded by darker coloured feldspar, bt and hbl, giving the core a gneissic appearance. The banding passes through the veins indicating it was a later process. Veining is similar in intensity to above interval.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other		From	To					
1	1	4.0	4.0																			B381388	8.23	8.63	<0.005			VA05070460	0.40
																						B381389	8.23	8.63	0.005	PD/CA		VA05070460	0.40
																						B381390	STANDARD 3C		0.142	3C		VA05070460	
0																							8.63	9.14			Broken - Poor recovery		0.51
3	1	0.2	0.6	20	140																		9.14	10.67					1.53
0																							10.67	12.19			Broken - Poor recovery		1.52
0																							12.19	13.72			Broken - Poor recovery		1.53
0																							15.24	16.76			Broken - Poor recovery		1.52
0																							16.76	18.29			Broken - Poor recovery		1.53
0																							18.29	19.81			Broken - Poor recovery		1.52
0																							19.81	21.34			Broken - Poor recovery		1.53
1	1	0.2	0.2	30									3.0					95.0					21.34	22.86			Crosscuts Foliation		1.52
0																							22.86	24.38					1.52
0																							24.38	25.91					1.53
	1	0.2																					25.91	27.43			Pieces		1.52
0																							27.43	28.96			Broken - Poor recovery		1.53
0																							28.96	30.48			Broken - Poor recovery		1.52
0																							30.48	32.00			Broken - Poor recovery		1.52
0																							32.00	32.73			Broken - Poor recovery		0.73
0																							32.73	33.53			Intense alt - veins not visible		0.80
0																							33.53	35.00			Intense alt - veins not visible		1.47
0																							35.00	36.58			Intense alt - veins not visible		1.58
0																							36.58	36.72			Intense alt - veins not visible		0.14
																							36.72	38.10					1.38
																							38.10	39.62					1.52
																							39.62	41.15					1.53
	1	2.0											0.1									B381391	41.15	42.67	0.005		Broken pieces	VA05070460	1.52
1	1	3.0	3.0	50						1.0								25.0				B381392	42.67	44.20	<0.005		Broken pieces	VA05070460	1.53
1	1	2.0	2.0	40						1.0								65.0				B381393	44.20	45.72	0.005			VA05070460	1.52
2	1	1.0	2.0	40						1.0								50.0				B381394	45.72	47.24	<0.005			VA05070460	1.52
1	1	1.5	1.5	70																		B381395	47.24	48.77	0.005			VA05070460	1.53
																						B381396	BLANK		<0.005			VA05070460	
2	1	6.0	10.0	60									10.0					50.0	50.0			B381397	48.77	50.29	0.019			VA05070460	1.52
3	1	9.0	15.0	30									1.0					75.0				B381398	50.29	51.82	0.007			VA05070460	1.53
3	1	8.0	17.0	50																		B381399	51.82	53.34	0.005		No visible sulphides	VA05070460	1.52
2	1	35.0	45.0	40									5.0						90.0			B381400	53.34	54.09	0.005			VA05070460	0.75
11	1	2.0	4.0	40	85					0.1												B381401	54.09	54.86	<0.005			VA05070460	0.77
																						B381402	54.09	54.86	<0.005	DUP		VA05070460	0.77
4	1	1.0	3.0	50																		B381403	54.86	55.40	<0.005		Crosscuts Foliation	VA05070460	0.54

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 3 of 12		
DRILL HOLE # : DG05-298C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70		58.63	60.96	QZZ - Same as previous QZZ interval, with a max vein size of 9cm.						
80		60.96	66.85	Silicious MSED - Dark grey. Qtz veins continue intensity and large size. Foliation @60.96m -> 50-52°, @62.48m -> 45-47°, @64.01m -> 50-55°, @65.53m -> 55-60° @66.35m - 10cm gouge. Contains angular 1-5cm MSED frags. No contact angle visible.		1	1			
70		66.85	68.58	QZZ - Light grey. Veins decrease in number to 2, and in size to a max of 0.2cm. Relic foliation is @45-50° to CA			1			
80		68.58	71.02	MSED - Dark grey, 40% argillite. Chl alt'n is increased, while ser alt'n decreases. Foliation @68.58m -> 45-47°, @70.10m -> 45-47°. There is an increase in veining compared to previous interval. @69.77m - conjugate vein set. 2cm grey qtz @60° and 115° to CA. 2cm bt selvage		1	2			
		71.02	72.25	Silicious MSED - same as above with a higher silica content. Likely due to contact with GND dyke @ 72.25m		1	2			
12	72.25 - 72.82	72.25	72.82	GND dyke - 30% qtz, 20% plag, 15% bt. Contact @20° to CA. The first 17cm of GND is bleached and contains only 1% bt. Veins are small (<0.2 cm) containing trace sulphides.						
80	72.82 - 95.49	72.82	88.79	MSED - Silicious, grey to dark grey. Veining is similar to previous MSED interval with a max of 4cm. Sulphide veins are present with 95% ranging from 0.1-0.2 cm Sulphides have been replaced by bt. Bt selvages are also common among qtz veins. Qtz and sulphide veinlets crosscut foliation. Foliation @72.82m -> 55-57°, @73.15m -> 50-52°, @74.68m -> 45-47°, @76.20m -> 40-45°, @77.12m -> 45-47°, @79.25m -> 50-55°, @80.77m -> 50-52°, @82.30m -> 60-62°, @83.82m -> 60-62°, @85.34m -> 60-62°, @86.87m -> 50-52°		1	1	1	1	
70		88.79	93.52	QZZ - Veining is reduced as is the sulphide content. Cb fills fractures. @90.36m - 29cm GND dyke @50° to CA. GND is bleached with 1% mafics present. Light green color, minor chl present.			1			
80		93.52	95.49	Silicious MSED - Dark grey, no major veining. Foliation @93.52m -> 60-62°, @94.49m -> 65-67°. @95.49m - contact with GND dyke @40° to CA		3	1	1	1	
12	95.49 - 95.89	95.49	95.89	GND Dyke - Light blue-grey color. Phaneritic, 10% bt, which is less than most GND in other holes. No visible veins.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
5	1	7.0	15.0	50									3.0						90.0			B381404	55.40	56.39	<0.005			VA05070460	0.99
6	1	0.5	3.0	60	115	0.1	b	2	0				0.1									B381405	56.39	57.91	<0.005		Aspy in selvages	VA05070460	1.52
6	1	1.0	2.5	50									0.1									B381406	57.91	58.63	0.005			VA05070460	0.72
3	1	0.2	0.6	35									1.0									B381407	58.63	59.44	<0.005			VA05070460	0.81
4	1	0.2	0.8	50						1.0										95.0		B381408	59.44	60.96	<0.005			VA05070460	1.52
																						B381409	59.44	60.96	<0.005	PD/CA		VA05070460	1.52
																						B381410	STANDARD 4D		0.450	4D		VA05070460	
6	1	6.0	11.0	60	130								1.0						95.0			B381411	60.96	62.48	<0.005			VA05070460	1.52
10	1	0.5	5.0	50		0.1	k	1	0				0.1						50.0			B381412	62.48	64.01	<0.005			VA05070460	1.53
5	1	5.0	11.0	55									0.1						50.0			B381413	64.01	65.53	<0.005			VA05070460	1.52
2	1	1.0	2.0	60									0.1									B381414	65.53	66.85	<0.005			VA05070460	1.32
2	1	0.2	0.4	50																		B381415	66.85	68.58	0.005			VA05070460	1.73
																						B381416	BLANK		<0.005			VA05070460	
4	1	2.0	6.0	60	115	2.0	b	4	0				3.0						95.0			B381417	68.58	70.10	<0.005			VA05070460	1.52
4	1	0.1	0.4	40									0.1						95.0			B381418	70.10	71.02	<0.005		Crosscuts Foliation	VA05070460	0.92
	1																					B381419	71.02	72.25	<0.005		Broken Pieces	VA05070460	1.23
4	1	0.1	0.4	45		0.1	q/k	2	0				0.1									B381420	72.25	72.82	0.005			VA05070460	0.57
2	1	1.0	1.5	45						0.1												B381421	72.82	73.15	0.006		Crosscut Foliation	VA05070460	0.33
																						B381422	72.82	73.15	0.008	DUP	Crosscut Foliation	VA05070460	0.33
5	1	1.5	4.5	50									0.1									B381423	73.15	74.68	0.010		Crosscut Foliation	VA05070460	1.53
2	1	0.5	1.0	45									0.1									B381424	74.68	76.20	<0.005		Crosscut Foliation	VA05070460	1.52
5	1	1.0	2.4	37																		B381425	76.20	77.72	0.006		Crosscut Foliation	VA05070460	1.52
6	1	1.0	4.0	50									1.0							90.0		B381426	77.72	79.25	0.005		Crosscut Foliation	VA05070460	1.53
4	1	1.5	3.0	50						0.1			0.1						10.0	90.0		B381427	79.25	80.77	<0.005		Crosscut Foliation	VA05070460	1.52
6	1	0.5	1.5	40									0.1							90.0		B381428	80.77	82.30	<0.005		Crosscut Foliation	VA05070460	1.53
																						B381429	80.77	82.30	<0.005	PD/CA		VA05070460	1.53
																						B381430	STANDARD 2B		3.270	2B		VA05070460	
3	1	1.0	1.4	30	60					1.0												B381431	82.30	83.82	<0.005		Crosscut Foliation	VA05070460	1.52
5	1	0.2	1.0	30		0.1	b	4	0				0.1									B381432	83.82	85.34	<0.005			VA05070460	1.52
4	1	0.2	0.8	30									0.1									B381433	85.34	86.87	<0.005			VA05070460	1.53
0																						B381434	86.87	88.39	0.005			VA05070460	1.52
1	1	3.0	3.0	50																		B381435	88.39	88.79	<0.005			VA05070460	0.40
																						B381436	BLANK		<0.005			VA05070460	
0																						B381437	88.79	89.92	0.097			VA05070460	1.13
0																						B381438	89.92	90.36	<0.005			VA05070460	0.44
1	6	0.1	0.1	25		0.1	b	4	0				0.1							95.0		B381439	90.36	90.60	0.005			VA05070460	0.24
1	1	6.0	6.0	70									0.1						95.0			B381440	90.60	91.44	0.025			VA05070460	0.84
3	1	2.0	2.4	60									0.1						95.0			B381441	91.44	92.96	<0.005			VA05070460	1.52
																						B381442	91.44	92.96	0.005	DUP		VA05070460	1.52
1	1	4.0	4.0	55									0.1						95.0			B381443	92.96	93.52	0.010			VA05070460	0.56
0																							93.52	94.49					0.97
0																							94.49	95.49					1.00
0																						B381444	95.49	95.89	<0.005			VA05070460	0.40

DRILL HOLE # : DG05-298C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80	95.89 - 208.39	95.89	104.91	Silicious MSED - Less silicious than previous intervals. Foliation becomes higher angle to CA. There is an increase in veining and sulphide concentrations. Py can be found on frac faces. Foliation @95.89m -> 64-67°, @96.01m -> 65-67°, @97.54m -> 55-60°, @99.06m -> 60-62°, @100.58m -> 67-70°, @102.11m -> 70-75°, @103.63m -> 70-72°, @105.16m -> 85-87° @103.63m - MSEDS are brecciated and cemented by carbonate. Intense ser on frac faces.						
70		104.91	112.94	QZZ - Shear Zone - QZZ is intensely altered and deformed. Core is brecciated and half is reduced to sand size grains of qtz. Qtz veins are the last to be deformed and 90% still visible. Veining is increased as are sulphide concentrations, though most are oxidized						
80		112.94	119.71	MSED - Dark grey to black, easy to scratch. Ser on frac faces. Chl occurs in bands of 5-20cm and is associated with veins. Veining is reduced from previous interval. Foliation @112.94m -> 50-55°, @114.30m -> 50-55°, @115.82m -> 45-50°, @117.35m -> 55-60°, @118.87m -> 35-40° @115.58m - 22cm SZ @ 10° to CA.		1	1		1	
70		119.71	123.24	QZZ - Light grey, increase in veins, 90% of sulphides oxidized. Residual foliation @ 45-60°, crenulated. Cb veinlets present and on frac faces.			1		1	
93		123.24	127.13	SZ - Sheared MSED and QZZ. Core appears brecciated and highly fractured. Intense argillic alt'n follows breccia. Contact angles range from 10-30°. Chl and ser alt'n also intense, but less than argillic. Cb alt'n is greater than chl and ser, but less than arg. Qtz veins present but are fracture or reduced to pebble sized pieces. Sulphides have been heavily oxidized (90%)		2	2	4	3	
80		127.13	138.88	Silicious MSED - Grey to dark grey. Increase in qtz veining but few visible sulphides. Qtz veins between foliations. Foliation @127.13m -> 50-60°, @128.02m -> 80-85° folded, @129.54m -> 40-45°, @131.06m -> 45-50°, @132.59m -> 40-45°, @134.11m -> 20-50 "s" shaped fold, @135.64m -> 57-60°, @137.16m -> 57-60°. Intense ser on frac faces. @138.78m - 3cm apl dyke @ 55° to CA		3	1	1	2	
70		138.88	147.05	QZZ & MSED - 80% QZZ with intermittent bands of silicious MSED 5-30cm long. The foliation in the MSEDS is crenulated or folded into "s" patterns, making it difficult to measure. Veining is reduced in this section. Contacts between QZZ and MSED do not have a preferred orientation. 90% are undulatory and random. @144.72m, 16cm APL dyke @45° to CA. Foliation where measurable @ 50-60°		1	2		1	
80		147.05	159.32	MSED & QZZ - 80% silicious MSED with bands of QZZ ranging from 10 - 60 cm in width. Veining is similar to previous interval and sulphides are not visible. MSEDS show less folding, but it is still present. Foliation @147.05m -> 40-42°, @147.83m -> 47-50°, @149.35m -> 47-50°, @150.88m -> 50-55°, @152.40m -> 45°, @153.92m -> 47°, @155.45m -> 49°, @156.97m -> 46°, @158.50m -> 53°. @ 151.95m - 84cm GND dyke @ 60° to CA. GND is bleached, with 1% bt present. Ser and CHL alt'n dominant. Two 0.1cm sulphide veinlets present @ 40° and 70° to CA.		2	1		1	
70		159.32	163.84	QZZ - Light grey. Increase in number and size of qtz veins (max 10cm). Chl alt'n is increased, more intensity around veins. Relic foliation is at lower angles to CA. Foliation @ 32° to CA. @ 160.08m - 10cm qtz vein @ 32° to CA. Chl on frac faces. @ 160.92m - 37cm HFLS. Cb veins present after HFLS <0.5cm @ 10-30° to CA			2		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date:_____August 7 - 13, 2005_____

LOGGED BY:_____Terry Croteau_____

PAGE _6_ of _12_

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	1	0.1	0.2	10																		B381445	95.89	97.54	0.005			VA05070460	1.65
0																						B381446	97.54	98.25	<0.005			VA05070460	0.71
2	1	1.0	1.2	75									0.1						90.0			B381447	99.06	100.58	<0.005			VA05070460	1.52
2	1	2.0	2.5	65									0.1						90.0			B381448	100.58	102.11	0.007			VA05070460	1.53
																						B381449	100.58	102.11	0.008	PD/CA		VA05070460	1.53
																						B381450	STANDARD 5E		1.535	5E		VA05070460	
2	1	1.0	2.0	40																		B381451	104.91	105.16	0.005			VA05070460	0.25
5	1	2.0	7.0	40									0.1					70.0				B381452	105.16	106.68	<0.005			VA05070460	1.52
4	1	3.0	8.0	30	60								0.1									B381453	106.68	108.20	0.013			VA05070460	1.52
1	1	1.0	1.0	30																		B381454	108.20	109.73	0.008			VA05070460	1.53
3	1	2.0	5.0	35									0.1									B381455	109.73	111.25	<0.005			VA05070460	1.52
																						B381456	BLANK		<0.005			VA05070460	
3	1	1.0	3.0	40									0.1					95.0				B381457	111.25	112.94	0.015			VA05070460	1.69
	1	2.0											1.0						90.0			B381458	115.12	116.52	<0.005			VA05070460	1.40
1	1	9.0	9.0	45									10.0						90.0			B381459	116.52	117.35	0.007			VA05070460	0.83
4	1	6.0	10.0	40									0.1						90.0			B381460	117.35	118.87	<0.005			VA05070460	1.52
2	1	4.0	9.0	40									0.1						90.0			B381461	118.87	119.71	0.006			VA05070460	0.84
																						B381462	118.87	119.71	<0.005	DUP		VA05070460	0.84
2	1	2.0	2.5	35																		B381463	119.71	120.40	<0.005			VA05070460	0.69
6	1	6.0	12.0	37									0.1									B381464	120.40	121.92	<0.005			VA05070460	1.52
4	1	2.0	3.0	75	40					0.1			0.1						75.0			B381465	121.92	123.24	<0.005			VA05070460	1.32
4	1	8.0	8.0	60									1.0						90.0			B381466	123.24	124.70	0.006		Sheared and broken	VA05070460	1.46
	1																					B381467	124.97	126.49	<0.005			VA05070460	1.52
	1																					B381468	126.49	127.13	<0.005			VA05070460	0.64
																						B381469	126.49	127.13	<0.005	PD/CA		VA05070460	0.64
																						B381470	STANDARD 4D		0.434	4D		VA05070460	
4	1	7.0	23.0	70									5.0						90.0			B381471	128.02	128.72	0.007			VA05070460	0.70
1	1	27.0	27.0	70									10.0						90.0			B381472	128.82	129.10	<0.005			VA05070460	0.28
3	1	2.0	5.0	60						0.1			0.1					25.0	90.0			B381473	129.59	131.06	<0.005			VA05070460	1.47
5	1	4.0	9.0	65						0.1			0.1					25.0	90.0			B381474	131.06	132.59	<0.005			VA05070460	1.53
5	1	3.0	8.0	60						0.1			0.1					25.0	90.0			B381475	132.59	134.11	<0.005			VA05070460	1.52
																						B381476	BLANK		<0.005			VA05070460	
4	1	2.5	5.0	80						0.1			0.1					25.0	90.0			B381477	134.11	135.22	<0.005			VA05070460	1.11
3	1	2.0	2.8	40									0.1						90.0			B381478	139.10	140.43	<0.005			VA05070460	1.33
2	1	9.0	11.0	70									0.1						90.0			B381479	149.35	149.65	<0.005			VA05070460	0.30
2	6	0.1	0.2	40	70								0.1							95.0		B381480	151.95	152.79	0.011			VA05070460	0.84
1	1	2.0	2.0	50																		B381481	159.32	160.02	0.006		No Visible Sulphides	VA05072073	0.70

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 7 of 12		
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		163.84	169.93	MSED interbedded with QZZ and HFLS - Foliation is initially at a higher angle to CA, but several small intrusions cause lower angles and folding. The small intrusive bodies (1-2cm) @ 165.50m and 166.32m are aplite. HFLS can be found surrounding them. Foliation @163.84m > 43°, @164.49m -> 45°, @166.12m -> 25°, @167.64m - not measureable, @169.16m -> not measurable. @165.50m - foliation @10°,40°, and 10° in "S" fold (see drawing ~)		2	2		2	
70		169.93	172.21	QZZ - Light grey-green, chl alt'n dominant. Few qtz veins, cb veins more common. Residual foliation @ 50° to CA, becoming 35° at end of interval		1	2			
80		172.21	176.41	MSED - Soft, easily scratchable. Foliation @ 35° increasing to 50° @ 174.74m @174.52m - 62cm GND dyke. Bleached and sericitized, 1% bt. Uphole contact not visible, downhole contact @ 80° to CA.		1	2		1	
12		176.41	178.01	GND dyke - Bleached, 5% bt, grey green color. Chl higher than ser alt'n, minor cb alt'n. Fractures @40° and 140°. Four 2cm qtz veins present, with trace aspy. Downhole contact @45° to CA.		2	3		3	
						2	3		3	
81		178.01	185.93	HFLS - Violet, green, white. Cb veining increased. Foliation still visible. Foliation @178.01m -> 37°, @178.31m -> 50°, @179.83m -> 45°, @181.36m -> 50°, @182.88m -> 50°, @184.40m -> 45°. Cb veins are at low angles, 10-25°. Very few veins in interval. No samples.						
81		185.93	190.76	HFLS & QZZ - Same as previous interval with an increase in QZZ and veining. Core contains 30% QZZ. Foliation @ 185.93m -> 40°, @187.45m -> 37°, @188.93m->45°, @190.50m -> too broken. Cb veining is reduced to 1 - 2 cm vein @ 25° to CA						
81		190.76	195.07	HFLS - Dark blue, with violet and green. There is a larger increase in veining with a max of 75cm. The sulphides also increase, but they are oxidized 50-90%. Scor and bt are common oxidation types.						
81		195.07	208.39	HFLS - Argillic alt'n becomes dominant form, chl also major alt'n. Cb alt'n increased. Qtz veining shows a large decrease in size (Max 3cm) and in number. Po, cpy and aspy found in veins. Foliation difficult to measure due to shearing. Gouge is also common: @ 195.95m - 15cm clay with qtz eyes and frags. @ 198.36m - 7cm clay with qtz eyes, MSED frags @ 204.84m - 0.5cm wide, 34 cm long gouge @12° to CA - slip plane @ 205.74m - 10cm gouge @30° to CA. Clay with MSED frags and ser Alteration becomes more intense after 207.47m where 70% of core shows argillic alt'n. Diss py, aspy, found throughout		2	3	3	2	
12	208.39 - 209.41	208.39	209.41	GND dyke - Light grey, 5% bt. Ser alt on frac faces. No visible qtz veins or structures as core is broken. Minor cb veinlets (2). Uphole contact not visible, downhole @70° to CA.		1			1	
81	209.41 - 243.36	209.41	215.82	Silicious HFLS - Grey, violet, green, dark blue. Hard, silicious, increased qtz content as veins and qtz eyes. Diss po found throughout. Minor potassic alt'n. Chl, ser on frac faces. Foliation @209.41m -> 30°, @210.31m -> 30°, @211.84m -> 40°, @213.36m -> 45°, @214.88m -> 45°		2	2		1	1

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	Sulphides: pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation: oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
																						B381482	159.32	160.02	0.009	DUP	No Visible Sulphides	VA05072073	0.70
1	1	10.0	10.0	32																		B381483	160.02	160.40	<0.005		No Visible Sulphides	VA05072073	0.38
4	1	2.0	7.0	45																		B381484	160.40	160.92	<0.005			VA05072073	0.52
3	1	2.0	6.0	47						1.0												B381485	161.54	163.07	0.005			VA05072073	1.53
1	1	0.2	0.2	60																		B381486	174.46	175.18	0.015			VA05072073	0.72
2	1	0.2	0.4	50									0.1									B381487	176.41	176.78	0.036			VA05072073	0.37
2	1	0.2	0.4	50									0.1									B381488	176.78	178.01	0.028			VA05072073	1.23
																						B381489	176.78	178.01	0.036	PD/CA		VA05072073	1.23
																						B381490	STANDARD 3C		0.091	3C		VA05072073	
2	1	2.0	4.0	40						0.1												B381491	185.93	187.45	0.007			VA05072073	1.52
4	1	2.0	5.0	50						0.1												B381492	187.45	188.98	<0.005			VA05072073	1.53
3	1	1.0	1.4	55						1.0			0.1									B381493	188.98	190.50	0.033			VA05072073	1.52
0										0.1			0.1									B381494	190.76	192.02	<0.005		Diss sulphides	VA05072073	1.26
2	1	15.0	25.0	65									1.0						90.0			B381495	192.02	192.56	<0.005			VA05072073	0.54
																						B381496	BLANK		<0.005			VA05072073	
2	1	75.0	95.0							1.0			1.0									B381497	192.56	193.55	<0.005			VA05072073	0.99
3	1	9.0	20.0										0.1									B381498	193.55	195.07	0.037			VA05072073	1.52
3	1	1.0	2.5	50						0.1			0.1									B381499	195.07	196.60	0.007		Diss sulphides	VA05072073	1.53
3	1	2.0	4.0	30						1.0												B381500	196.60	198.12	0.005		Py in vein and diss	VA05072073	1.52
5	1	1.5	6.0	35						0.1								75.0				B381501	198.12	199.64	<0.005			VA05072073	1.52
																						B381502	198.12	199.64	<0.005	DUP		VA05072073	1.52
1	1	0.2	0.2	30						1.0			1.0									B381503	199.64	201.17	0.005		Diss sulphides	VA05072073	1.53
5	1	0.2	1.0	27									0.1					75.0				B381504	201.17	202.69	0.010		Crosscuts foliation	VA05072073	1.52
1	1	2.0	2.0	60									5.0						90.0			B381505	202.69	204.22	0.011			VA05072073	1.53
4	1	1.0	2.5	30							3.0							90.0				B381506	204.22	205.74	<0.005		Crosscuts foliation	VA05072073	1.52
2	1	3.0	4.0	30							3.0	1.0	1.0									B381507	205.74	207.26	0.005		Crosscuts foliation	VA05072073	1.52
1	1	1.5	1.5	60									0.1						90.0			B381508	207.26	208.39	<0.005			VA05072073	1.13
																						B381509	207.26	208.39	<0.005	PD/CA		VA05072073	1.13
																						B381510	STANDARD 2B		2.970	2B		VA05072073	
2	4	0.1	0.1	30																		B381511	208.39	209.41	0.008		Veinlets	VA05072073	1.02
1	1	0.5	0.5	40									1.0						90.0			B381512	209.41	210.31	<0.005			VA05072073	0.90
2	1	0.5	1.0	50							0.1		0.1						90.0			B381513	210.31	211.84	<0.005			VA05072073	1.53
7	1	6.0	20.0	40	140	2.0	Chl	4	0		1.0											B381514	211.84	213.36	<0.005		Po is diss and in selvage	VA05072073	1.52
5	1	2.0	6.0	50		0.5	chl	4	0		0.1											B381515	213.36	214.88	<0.005		Po is diss and in vein	VA05072073	1.52
																						B381516	BLANK		<0.005			VA05072073	
2	1	2.0	3.0	50		0.5	chl	4	0		0.1											B381517	214.88	215.82	0.026		Crosscuts foliation, po in veins and diss	VA05072073	0.94

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 9 of 12		
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
61		215.82	231.65	HFLS - Dark blue-grey to black. Poikiloblastic texture common. Core contains 10-15% bt, 10% andalusite -> biotite-andalusite HFLS. Cb present on 90% of frac faces. Cb also dominant form of veins (60%). Qtz veining increased from previous interval, as well there is a corresponding increase in sulphides. Residual foliation is crenulated and crosscut by the veins. Qtz veins follow foliation. @227.08m - 40 cm GND dyke. 15% bt, no qtz veins, cb veins present. Uphole contact @35°, downhole contact @40° to CA		2	3	1	3	
81		231.65	237.74	HFLS - Intensely altered. Ser on frac faces. Cb is pervasive and on frac faces. Foliation @231.65m -> 50°, @233.17m -> 25°, @234.70m -> 25°, @236.22m -> 27° @231.89m, 7cm gouge, clay rich with HFLS frags		2	1	2	3	
81		237.74	240.79	Silicious HFLS - Pervasive Cb is increased. Core is highly fractured. Alteration obscures most foliation. @239.27m - Core becomes powdery on surface, argillic alt'n increased with ser and chl. Transitional before GND		2	1	2	4	
81		240.79	243.36	Gouge - Core is white, and intensely altered to clay. Crumbles when touched. Fragments in gouge are QZZ. Transition zone between HFLS and GND. Residual foliation @242.32m -> 55° to CA. Cb is pervasive. No visible veins		2	2	4	4	
10	243.36 - 280.42	243.36	245.36	GND - 30% qtz, 35% plag, 15% bt, 15% kspar, 5% hbl. Core is initially bleached, cb pervasive, only 5% mafics. By 243.84m is 90% unaltered. @ 243.84m - recovery poor (19%), core is broken into rounded gravel sized pieces.		2		3	4	
10		245.36	257.56	GND - 70% unaltered GND. Cb in veinlets and pervasive. Chl can be found on frac faces. Small (<0.5 cm) sheeted vein sets make their first appearance, as do aspy veinlets. There is an increase in aspy and po in the veins, compared to previous intervals. Fractures are @45° (parallel to veining) and 145° (crosscut veining).			1		2	
10		257.56	271.27	GND - Same as previous interval, but contains less pervasive cb. The larger veins (>2cm) occur in areas of chloritic alt'n, which has also increased on fracture faces. @262.88m - Slickensides on 40° frac faces @80° from CA			2		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	2.0	2.0	45							5.0	0.1	0.1									B381518	215.82	216.40	0.025		Large euhedral aspy (.3 cm)	VA05072073	0.58
4	1	0.5	2.0	50							3.0	0.1	1.0						90.0			B381519	216.40	217.93	0.088			VA05072073	1.53
4	1	5.0	14.0	35							1.0		1.0						50.0			B381520	217.93	219.46	0.018			VA05072073	1.53
3	4	1.0	1.4	120																									
6	1	6.0	13.0	50							0.1		5.0						90.0			B381521	219.46	220.98	<0.005			VA05072073	1.52
																						B381522	219.46	220.98	<0.005	DUP		VA05072073	1.52
2	1	1.0	2.0	60							0.1		0.1									B381523	220.98	222.50	0.009			VA05072073	1.52
10	4	0.2	2.0	120																									
1	1	1.0	1.0	60									0.1									B381524	222.50	224.03	0.030			VA05072073	1.53
8	4	0.5	1.9	120																									
3	1	2.0	3.0	35									0.1						90.0			B381525	224.03	225.55	0.042			VA05072073	1.52
5	4	1.0	4.0	35																		B381526	225.55	227.08	0.017			VA05072073	1.53
3	1	2.0	4.0	25						1.0								50.0				B381527	227.08	228.60	0.020			VA05072073	1.52
5	4	0.5	1.3	120																									
4	1	4.5	8.0	30						1.0			0.1					50.0				B381528	228.60	230.12	0.009			VA05072073	1.52
																						B381529	228.60	230.12	0.014	PD/CA		VA05072073	1.52
																						B381530	STANDARD 5E		1.440	5E		VA05072073	
1	3	1.0	1.0	50									0.1					50.0				B381531	230.12	231.65	0.005			VA05072073	1.53
9	4	0.2	1.8	130	170																								
2	1	0.2	0.4	50									0.1									B381532	231.65	233.17	<0.005			VA05072073	1.52
3	1	0.2	0.6	55									0.1									B381533	233.17	234.70	0.017			VA05072073	1.53
3	1	0.2	0.6	50																		B381534	234.70	236.22	0.012			VA05072073	1.52
5	1	0.2	1.0	55									0.1									B381535	236.22	237.74	<0.005			VA05072073	1.52
																						B381536	BLANK		<0.005			VA05072073	
7	1	0.2	1.4	50	85								0.1									B381537	237.74	239.27	0.008			VA05072073	1.53
2	1	0.2	0.4	55									0.1									B381538	239.27	240.79	0.010			VA05072073	1.52
0																						B381539	240.79	242.32	0.051			VA05072073	1.53
0																						B381540	242.32	243.36	0.033			VA05072073	1.04
0																						B381541	243.36	243.84	0.216			VA05072073	0.48
																						B381542	243.36	243.84	0.036	DUP		VA05072073	0.48
	1									0.1												B381543	243.84	245.36	0.012			VA05072073	1.52
4	1	3.0	3.6	35	45					1.0			3.0									B381544	245.36	246.89	0.043			VA05072073	1.53
4	1	2.0	3.9	45	70	0.2	k	3	0		1.0		5.0									B381545	246.89	248.41	0.114			VA05072073	1.52
8	1	0.5	2.2	45		0.2	q	3	0	0.1			10.0									B381546	248.41	249.98	0.094			VA05072073	1.57
3	1	1.0	1.4	45		0.2	q	3	0		0.1											B381547	249.98	251.46	0.061			VA05072073	1.48
3	1	1.0	1.4	45						1.0	0.1		5.0									B381548	251.46	252.98	0.085			VA05072073	1.52
																						B381549	251.46	252.98	0.095	PD/CA		VA05072073	1.52
																						B381550	STANDARD 6F		2.850	6F		VA05072073	
2	1	0.2	0.4	45							0.1	0.1	1.0									B381551	252.98	254.51	0.080			VA05072073	1.53
0																						B381552	254.51	256.03	0.033			VA05072073	1.52
4	1	0.2	0.8	45	10						3.0		1.0									B381553	256.03	257.56	0.087		More po present in low angle veins	VA05072073	1.53
2	1	2.0	4.0	45									0.1									B381554	257.56	259.08	0.098			VA05072073	1.52
6	1	3.0	5.2	57		4.0	chl	3	0	1.0			3.0									B381555	259.08	260.60	0.048		Aspy in vein and selvage	VA05072073	1.52
																						B381556	BLANK		<0.005			VA05072073	
5	1	2.4	2.4	50		5.0	chl	3	0		1.0	0.1	3.0									B381557	260.60	262.13	0.032		Aspy in vein and selvage	VA05072073	1.53
2	1	1.5	1.7	47									1.0									B381558	262.13	263.65	0.066			VA05072073	1.52

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-298C	FeOx 0 = Unoxidized 5 = Intensely Ox'd Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
11		271.27	275.84	GND - Finer grain size compared to previous interval. Increase in pervasive cb. Contains 25-30% mafics. There is a decrease in the number of qtz veins over this interval, but similar sulphide content. Fractures occur @30° and 40° to CA.			1		2	
10		275.84	278.89	GND - return to med grain-size. 70% of core shows chl alt'n. Veins increase in number, size and sulphide content. @277.37m - Core shows hydrothermal alt'n - clay with GND frags and qtz pebbles. Contact @ 20° to CA. @278.24m - 10cm grey qtz vein @35° to CA. Contains 3% aspy		1	3	2	1	
10		278.89	280.42	GND - Becomes coarse grained, 20% of core shows chl alt'n. @278.89m - 15cm grey qtz vein @ 60° to CA. 3% aspy @280.16m - core is 10% diss po.			2			
	EOH									

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	6	0.1	0.1	50									70.0																
7	1	0.2	1.4	40							3.0											B381559	263.65	265.18	0.024			VA05072073	1.53
6	1	2.0	3.8	30	20	2.0	chl	3	0				5.0									B381560	265.18	266.70	0.253			VA05072073	1.52
3	1	0.2	0.6	35									20.0									B381561	266.70	268.22	0.261			VA05072073	1.52
																						B381562	266.70	268.22	0.309	DUP		VA05072073	1.52
5	1	1.5	3.9	42									30.0									B381563	268.22	269.75	0.184			VA05072073	1.53
3	1	1.0	1.2	50									5.0									B381575	269.75	271.27	0.065		Missed Sample	VA05072073	1.52
1	1	1.0	1.0	35									10.0									B381564	271.27	272.80	0.156			VA05072073	1.53
2	1	0.2	0.2	40									5.0						50.0			B381565	272.80	274.32	0.057			VA05072073	1.52
5	1	2.0	4.5	35							1.0											B381566	274.32	275.84	0.015			VA05072073	1.52
5	1	1.0	3.2	25																		B381567	275.84	277.37	0.289			VA05072073	1.53
0																						B381568	277.37	278.24	0.334		Not visible due to alt	VA05072073	0.87
																						B381569	277.37	278.24	4.460	PD/CA		VA05072073	0.87
																						B381570	STANDARD 7G		13.900	7G		VA05072073	
1	1	10.0	10.0	35									3.0									B381571	278.24	278.34	1.050			VA05072073	0.10
0																						B381572	278.34	278.89	6.900		Not visible due to alt	VA05072073	0.55
1	1	15.0	15.0	60									3.0									B381573	278.89	278.94	0.029			VA05072073	0.05
2	1	0.2	0.4	35							10.0		1.0									B381574	278.94	280.42	0.079		Po is diss	VA05072073	1.48
																						B381576	BLANK		0.137			VA05072073	
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-299C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:

BEARING: 000 | DIP: -50°

DATE STARTED: 26-Jul-05 | DATE COMPLETED: 30-Jul-05

LOGGED BY: Kevin Piepgrass (Aug 7 - 14, 2005)

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459658 NORTHING: 7099319

COORD SYSTEM: NAD 83: EASTING: 459539 NORTHING: 7099505

NAD 27 (CORRECTED for historic grid): EASTING: 459628 NORTHING: 7099329

SECTION LINE(historic grid): 459628 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 3.35m

Deviation:

Casing: 3.35m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B363324 - B363423

Requisition #: MASP448STRGOL.05Q | Date Shipped: 13-Aug-05

Lab Record #: VA05070531 | Date Received: 23-Aug-05

Sample Sequence: B363424 - B363552

Requisition #: MASP448STRGOL.05Q | Date Shipped: 14-Aug-05

Lab Record #: VA05070461 | Date Received: 22-Aug-05

Duplicates:	363342; 363362; 363382; 363402; 363422; 363442; 363462; 363482; 363502; 363522; 363542
Preparation Duplicate/ Check Assay:	363329; 363349; 363369; 363389; 363409; 363429; 363449; 363469; 363489; 363509; 363529; 363549
Standards:	363330 (3C); 363350 (4D); 363370 (1A); 363390 (6F); 363410 (4D); 363430 (5E); 363450 (2B); 363470 (3C); 363490 (5E); 363510 (4D); 363530 (3C); 363550 (1A)
Blanks:	B363337, B363356, B363376, B363396, B363416, B363436, B363456, B363476, B363496, B363516, B363536

FROM	TO	LITHOLOGY
3.35	67.06	MSED
67.06	294.13	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	AZ (+27 Corr)
201.2	340.5	-58.1	006.5	007.5
294.1	340.9	-57.7	006.9	007.9

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2006	PAGE 1 of 12		
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-3.35	0.00	3.35	Casing, No core						
80	3.35-21.67	3.35	10.67	Silicified sed (quartzite). Moderate qtz vning with few vns x-cutting. Core appears to have a pinkish colour to it (possibly k-spar alt'n?).	3					
80		10.67	21.67	Much of core is highly fractured with limonite on fractured surfaces. Coherent core is darker with near parallel qtz vning and foliation between 60° and 45° to CA. Core that appears darker is less oxidized. Qtz vn selvages have pinkish colour possibly due to k-spar alt'n.	3					
80	21.67-67.06			Most of core has been intensely alt'd to clay with remnant qtz eyes or vn's. There are few intervals of dark fol'd core (as above). The clay alt'd core tends to be more ox'd (limonite) than dark MSED.	3			4		
80		39.00	41.00	Dark fol'd MSED. Fol'n gradually changes (down hole) from 1-30°. Fresher qtz vn's x-cutting fol'n at 70° to CA. Qtz vn's still ox'd but contain fresh f.g. py (1-2%). White laths (plag?) present along fol'n planes.	2					
80		41.00	44.20	Clay-rich broken core with short (20cm) intervals of dark fol'd MSED.	4			4		
80		44.20	44.83	Dark MSED with fol'n from 0 to 30°.	2					
80		45.70	46.80	Incoherent clay-rich core (fault gouge?)						
80		52.48	52.92	Dark MSED with fol'n about 30°.	2					
80		60.96	67.06	Broken up Quartzite. Size of blocks vary from mm-scale to 10cm in length.	2			1		
10	67.06-81.40	67.06	72.17	Highly frac'd GND with limonite on all frac faces. Frac'd blocks are coherent. Locally alt'd to clay (5cm flt gg?). Ox'd frac faces tend to be filled with carb.	2			1		
10		72.17	81.40	GND is intensely alt'd and frac'd with lim on faces. GND is incompetent (crumbly). Abundant carb frac filling. At 77.62m slip face at 60° with lines at 70° to CA.	3			3	2	
10	81.40-83.40	81.40	83.40	Grey GND, mod frac'd with limonite on frac faces. Multiple mm-scale limonitic frac's (~45°). Gradually fades into ser/chl alt and carb alt. Five near parallel vn's (carb, qtz and cb/q) within 30cm with ser alt'n in middle and chl alt'n surrounding. Slip face at edge of chl alt'n: 60° face with 60° lines.		3			3	
10	83.40-114.30	83.40	114.30	Back into grey GND. High % vning - mostly qtz with some carb. Qtz vns have small selvages. Possible VG mixed in with po and cpy. Thin cb vnlts tend to have wide ser selvages overprinting some qtz vns. Local areas of greater frac'ing with carb alt'n/frac filling (10-50cm). At 88.79m: a 5cm clay alt'n (flt gg?). Slip faces: at 99.36m: face at 60° and lines at 70°, at 114.00m: face at 30° and lines at 50°.		1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																			
						Selvages				Sulphides									Oxidation					Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	1.0	1.0	30														2.0				B363324	3.35	4.57	0.009			VA05070531	1.22
3	1	1.0	2.5	30	60					1.0								2.0				B363325	4.57	6.10	<0.005			VA05070531	1.53
3	1	0.4	1.0	10	45	0.2	q	5										30.0				B363326	6.10	7.62	<0.005			VA05070531	1.52
6	1	1.0	2.0	45	30	0.2	q	4		1.0								20.0				B363327	7.62	9.14	0.011			VA05070531	1.52
4	1	1.0	2.0	30														2.0				B363328	9.14	10.67	0.012			VA05070531	1.53
	6																												
4	1	1.0	2.0	30														2.0				B363329	9.14	10.67	0.009	PD/CA		VA05070531	1.53
																						B363330	STANDARD 3C		0.081	3C		VA05070531	
0																						B363331	10.67	12.19	0.019			VA05070531	1.52
0																						B363332	12.19	13.72	0.008			VA05070531	1.53
2	1	3.0	4.0	10		0.5	q	3	1									10.0				B363333	13.72	15.24	0.053			VA05070531	1.52
3	1	1.0	2.5	70														20.0				B363334	15.24	16.76	0.006			VA05070531	1.52
5	1	2.0	6.0	60	30													10.0				B363335	16.76	18.29	<0.005			VA05070531	1.53
																						B363336	BLANK		<0.005			VA05070531	
3	1	4.0	7.0	45														5.0				B363337	18.29	19.81	<0.005			VA05070531	1.52
0																							19.81	21.67					1.86
0																							21.67	36.14					14.47
3	1	2.0	3.0	45														5.0				B363338	36.14	36.58	<0.005			VA05070531	0.44
0																							36.58	39.00					
6	1	1.5	5.0	45	70					2.0								5.0				B363339	39.00	40.51	0.27			VA05070531	1.51
3	1	4.0	4.5	70	30													5.0				B363340	40.51	41.93	0.005			VA05070531	1.42
0																							41.93	44.20					2.27
0																							44.20	60.96					16.76
0																													
0																													
0																						B363341	60.96	62.48	<0.005			VA05070531	1.52
																						B363342	60.96	62.48	<0.005	DUP		VA05070531	1.52
																						B363343	62.48	64.01	0.034			VA05070531	1.53
0																						B363344	64.01	65.53	<0.005			VA05070531	1.52
0																						B363345	65.53	67.06	0.006			VA05070531	1.53
2	1	1.0	1.5	30	45	0.5	q	4	3									4.0				B363346	67.06	68.58	0.033			VA05070531	1.52
0																						B363347	68.58	70.10	0.037			VA05070531	1.52
3	1	1.0	2.0	45		0.5	q/chl	4	3	0.1			0.1					5.0	1.0			B363348	70.10	71.63	0.089			VA05070531	1.53
3	1	1.0	2.0	45		0.5	q/chl	4	3	0.1			0.1					5.0	1.0			B363349	70.10	71.63	0.069	PD/CA		VA05070531	1.53
																						B363350	STANDARD 4D		0.43	4D		VA05070531	
0																						B363351	71.63	73.15	0.061			VA05070531	1.52
0																						B363352	73.15	74.68	0.25			VA05070531	1.53
0																						B363353	74.68	76.20	0.087			VA05070531	1.52
0																						B363354	76.20	77.72	0.042			VA05070531	1.52
0																						B363355	77.72	79.25	0.063			VA05070531	1.53
																						B363356	BLANK		<0.005			VA05070531	
1	1	0.5	0.5	45		2.5	s/cb	4	4		1.0							3.0				B363357	79.25	80.77	0.066			VA05070531	1.52
0																						B363358	80.77	81.40	0.026			VA05070531	0.63
1	1	0.5	0.5	30						1.0												B363359	81.40	82.00	0.026			VA05070531	0.60
3	4	2.0	3.5	30	45						1.0		1.0					20.0	5.0			B363360	82.00	83.40	0.438			VA05070531	1.40
1	1	1.0	1.0	30									1.0					5.0	1.0										
3	3	0.2	0.6	10		0.5	cb/s	5	4		1.0							80.0											
9	1	1.5	5.0	30	45	0.5	Q	4			2.0	0.1	1.0					1.0	2.0			B363361	83.40	85.34	0.084			VA05070531	1.94
4	4	0.3	0.7	30	45	3.0	s/cb	4	2									90.0											
9	1	1.5	5.0	30	45	0.5	Q	4			2.0	0.1	1.0					1.0	2.0			B363362	83.40	85.34	0.145	DUP		VA05070531	1.94
4	4	0.3	0.7	30	45	3.0	s/cb	4	2									90.0											
3	1	0.4	1.0	10	45	0.2	q	4	1				2.0					1.0	1.0			B363363	85.34	86.87	0.058			VA05070531	1.53

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2005 PAGE 3 of 12	
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		95.64	97.16	Sample B363372 - heavily frac'd core and limonite. Remnant qtz vn's with euhedral aspy up to 0.4 x 0.2mm. Also, abundant cb frac's.	1					
10	114.30-120.40	114.30	120.40	Similar grey GND but with multiple zones of intense ser alt. Zones up to 75cm long (ser alt'n more intense in middle of zone commonly with limonite selvage among fractures). Fractures: at 119.60m - face at 70° and lines at 70°, at 119.80m - face at 40° and lines at 50°, at 117.76m - face at 10° and lines at 10°, at 114.40m - face at 10° and lines at 10°, at 114.41m - face at 60° and lines at 45°, and at 114.70m - face at 70° and lines at 80°. Carb frac filling still present but less abundant than above. Contact between GND and ser alt'n is distinct. Qtz vn'ing is slightly less abundant than above. Alt'n most likely due to fracturing.		5				
10	120.40-130.06	120.40	130.06	Back into grey GND (similar to 83.40-114.30m). Limonite and carb frac filling are becoming less prominent. Frac faces/slip faces are of limonite, carb or chl. Slickenlines are fairly abundant: at 124.57m-face at 45° lines at 45°, at 126.49m-face at 30°, lines at 60°, at 127.50m-face at 50°, lines at 50°, at 128.02m-face at 30° lines at 10°, at 129.34m-face @10° lines at 30°, and at 129.34m-face 30° w/ lines at 45°. Majority of qtz vn'ing is near parallel except at 129.84m where vn's are x-cutting.					1	
10	130.06-132.45	130.06	132.45	GND is much lighter in colour and softer and is carb-rich. Very minor qtz vn'ing. Sharp contact with grey GND. At 130.80m slip face at 10° with lines at 10° to CA.					3	
10	132.45-137.70	132.45	137.70	Grey GND with minor qtz vn'ing and minimal alt. Slip faces occur at 132.87m on 20° face w/ lines at 20°, at 133.72m on 70° face with 80° lines, and at 135.92m on 45° face and 45° lines						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
10	1	1.0	6.5	30	45	4.0	chl	4			3.0	0.1	1.0									B363364	86.87	88.39	0.418			VA05070531	1.52
5	1	1.0	4.0	30	45	0.2	q	5			2.0	0.1	0.1					0.1	0.1			B363365	88.39	89.92	0.406			VA05070531	1.53
3	4	0.5	1.0	45	30	6.0	s/chl	5										90.0											
2	1	1.0	2.0	45							0.1							0.1	0.1			B363366	89.92	90.66	0.023			VA05070531	0.74
0																						B363367	90.66	92.00	0.048		Broken Core	VA05070531	1.34
5	1	1.0	4.0	30	60	1.0	q/s	5	1		1.0	0.1	0.1					1.0				B363368	92.00	92.96	0.06			VA05070531	0.96
5	1	1.0	4.0	30	60	1.0	q/s	5	1		1.0	0.1	0.1					1.0				B363369	92.00	92.96	0.042	PD/CA		VA05070531	0.96
																						B363370	STANDARD 1A		0.829	1A		VA05070531	
6	1	1.0	2.5	45	10						1.0		0.1					1.0	0.1			B363371	92.96	94.49	0.093			VA05070531	1.53
7	1	1.0	3.0	10	60						1.0								1.0			B363372	94.49	95.64	0.099			VA05070531	1.15
0																						B363373	95.64	97.16	0.297		broken core	VA05070531	1.52
5	1	1.0	4.0	60	45						1.0							1.0	2.0			B363374	97.16	98.34	0.047			VA05070531	1.18
2	1	0.5	1.0	30						0.1	1.0							1.0				B363375	98.34	99.76	0.047			VA05070531	1.42
																						B363376	BLANK		<0.005			VA05070531	
4	1	0.5	2.0	30	45						5.0		0.1					1.0	1.0			B363377	99.76	100.58	0.051			VA05070531	0.82
0																						B363378	100.58	101.58	0.065		broken core	VA05070531	1.00
6	1	1.0	3.0	45	30						1.0							1.0	2.0			B363379	101.58	102.86	0.054			VA05070531	1.28
2	1	1.0	1.5	45							0.1							1.0	1.0			B363380	102.86	104.56	0.059			VA05070531	1.70
8	1	1.0	4.0	30	45	0.4	q/s	3			2.0	1.0	0.1					1.0	1.0			B363381	104.56	105.81	0.281			VA05070531	1.25
8	1	1.0	4.0	30	45	0.4	q/s	3			2.0	1.0	0.1					1.0	1.0			B363382	104.56	105.81	0.605	DUP		VA05070531	1.25
2	1	1.0	1.8	30	45						0.1											B363383	105.81	107.16	0.033			VA05070531	1.35
2	4	0.3	0.5	30	45	1.0	q	5	2									90.0											
2	1	3.0	4.0	45		0.3	q	5										1.0				B363384	107.16	108.20	0.038			VA05070531	1.04
0																						B363385	108.20	109.73	0.026		broken core	VA05070531	1.53
2	1	4.0	5.0	30							1.0							1.0				B363386	109.73	111.25	0.06			VA05070531	1.52
5	1	2.0	4.0	30		0.3	Q	5			1.0		2.0					1.0	1.0			B363387	111.25	112.78	0.068			VA05070531	1.53
6	1	2.0	6.0	30							2.0	0.1	1.0					1.0				B363388	112.78	114.30	0.191			VA05070531	1.52
2	6	0.5	0.7	1	90	0.5	q	3	2		50.0	2.0	2.0					20.0											
6	1	2.0	6.0	30							2.0	0.1	1.0					1.0				B363389	112.78	114.30	0.181	PD/CA		VA05070531	1.52
2	6	0.5	0.7	1	90	0.5	q	3	2		50.0	2.0	2.0					20.0											
																						B363390	STANDARD 6F		2.76	6F		VA05070531	
1	1	1.0	1.0	10							1.0							3.0	1.0			B363391	114.30	115.82	0.057			VA05070531	1.52
1	1	0.3	0.3	30		1.0	q	3		0.1	3.0		1.0					1.0	1.0			B363392	115.82	117.10	0.008			VA05070531	1.28
1	1	2.0	2.0	5							2.0		1.0					1.0				B363393	117.10	117.76	0.479			VA05070531	0.66
5	1	2.0	6.0	30	1	0.5	s	3	1		4.0	1.0						1.0	2.0			B363394	117.76	118.87	0.086			VA05070531	1.11
0																						B363395	118.87	120.40	0.071		Intense Alteration	VA05070531	1.53
																						B363396	BLANK		<0.005			VA05070531	
2	1	1.5	2.5	45							3.0	1.0										B363397	120.40	121.92	0.014			VA05070531	1.52
3	1	2.0	4.0	30							3.0	0.1							1.0			B363398	121.92	123.44	0.17			VA05070531	1.52
5	1	1.5	3.0	30							2.0		1.0						1.0			B363399	123.44	124.97	0.399			VA05070531	1.53
1	1	1.0	1.0	45							0.1								0.1			B363400	124.97	126.49	0.02			VA05070531	1.52
5	1	1.0	4.0	40	30					0.1	2.0	1.0	0.1									B363401	126.49	128.02	0.232			VA05070531	1.53
1	6	0.4	0.4	30		0.5	q	4		1.0	80.0	5.0	1.0																
5	1	1.0	4.0	40	30					0.1	2.0	1.0	0.1									B363402	126.49	128.02	0.059	DUP		VA05070531	1.53
1	6	0.4	0.4	30		0.5	q	4		1.0	80.0	5.0	1.0																
3	1	1.0	2.0	30	45	0.5	q/s	5			5.0	1.0	1.0									B363403	128.02	129.54	0.035			VA05070531	1.52
2	6	0.3	0.5	45		0.5	q	5			30.0	5.0	50.0																
4	1	4.0	8.0	40	130	0.5	q/s	5			1.0		0.1									B363404	129.54	130.06	0.028			VA05070531	0.52
1	1	0.5	0.5	60																		B363405	130.06	131.06	0.018			VA05070531	1.00
3	1	0.5	1.5	45	60	0.5	s	3			1.0								1.0			B363406	131.06	132.45	0.029			VA05070531	1.39
3	1	5.0	6.0	45	2						1.0											B363407	132.45	134.11	0.02			VA05070531	1.66
5	1	0.5	2.0	45							2.0								1.0			B363408	134.11	135.64	0.024			VA05070531	1.53
5	1	0.5	2.0	45							2.0								1.0			B363409	134.11	135.64	0.034	PD/CA		VA05070531	1.53

DRILL LOG LEGEND - P1	DATE: July 26th to 30th, 2006	PAGE 5 of 12	
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	137.70-152.40	137.70	152.40	GND continuously changes from relatively unalt'd GND. Carb alt'n have sharp contacts with GND. Contacts commonly have slip surfaces. At 137.70m slickenlines at 80°, at 141.73 m with lines at 85°, at 142.00m, lines at 85°, @147.83m lines at 85°, at 148.90m lines at 60°, at 150.78m with lines at 75°. Carb alt'd core is softer and lighter in colour - locally intensely alt'd to carb/clay. Py smearing on slip faces. Minimal limonite on frac'd core. Most qtz vn's are < 1cm wide.					4	
10		152.40	165.49	Grey, relatively unaltered GND with multiple near parallel quartz veins; Qtz vns are thicker but do not contain much sulphides; Sericite alteration selvages are common among thicker (>2cm) veins; Only one occurrence of pyrite vein surrounded by 3cm sericite selvage occurring along fracture; Fractures commonly associated with thick (~3cm) sericite selvages; Slickenlines also common; At 155.55m = Face at 40° with lines at 45° TCA; At 156.67m = face at 45° with lines at 60° TCA: At 156.88m = face at 45° with lines at 80° TCA: At 161.40m = face at 60° with lines at 75° TCA; Local carbonate "fault gouge"(?) at 159.1m and 60°.		1			1	
10		165.49	181.36	Carbonate altered GND; GND is softer and lighter color; Local intervals of sericite alteration (166.32 - 167.64m); Short local intervals of mostly unaltered GND; Sericite alteration also occurs as selvages for fractures; Quartz veining is minimal but dominantly 45° TCA; Abundant factures with slickenlines preserved at.....165.70m = Fractured at 70° and lines at 85°; At 166.0m = fractured at 30° and lines at 45°; At 167.5m = fractured at 10° with lines at 70°; At 168.6m = fractured at 30° with lines at 55°; At 169.75m = fractured at 60° with lines at 70°; At 174.2m = fractured at 30° with lines at 40°; At 176.0m = fractured at 45° with lines at 70°; At 177.1m = fractured at 45° with lines at 80° TCA; At 179.12m = fractured at 40° with lines at 45° TCA; At 181.0m = fracture foliation at 60° with lines at 60°.		1			3	
10		181.36	191.04	Grey GND with minor to moderate carbonate alteration throughout; Sericite alteration is also apparent in short intervals (30cm); Multiple slip faces.....At 182.18m = fracture foliation at 45° with slickinlines at 70°; At 185.63m = fol'n at 45° with lines at 65°; At 186.13m = fol'n at 10° with lines at 10°; At 186.75m = fol'n at 60° with lines at 75°; At 188.88m = fol'n at 50° with lines at 70°; At 190.4m fol'n at 40° with lines at 90° TCA.		1			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

PAGE 6 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval					
						Selvages				Sulphides								Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
																						B363410	STANDARD 4D		0.456	4D		VA05070531	
6	1	1.0	2.5	45	30	1.0	s/q	3			2.0		0.1						2.0			B363411	135.64	137.70	0.032			VA05070531	2.06
1	1	1.0	1.0	45							2.0		1.0									B363412	137.70	138.68	0.041			VA05070531	0.98
5	1	2.0	5.5	45	60	0.5	q	5			1.0	0.1						2.0				B363413	138.68	140.21	0.031			VA05070531	1.53
1	6	0.5	0.5	45							30.0		10.0					5.0	5.0										
5	1	1.5	4.5	45							2.0		1.0									B363414	140.21	141.73	0.033			VA05070531	1.52
1	1	1.0	1.0	45							1.0							1.0				B363415	141.73	143.26	0.019			VA05070531	1.53
																						B363416	BLANK		<0.005			VA05070531	
4	1	0.5	1.5	30	45	0.5	Q/S	4			1.0		2.0						2.0			B363417	143.26	144.78	0.031			VA05070531	1.52
5	1	1.0	3.0	45	30						1.0		1.0					1.0	1.0			B363418	144.78	146.30	0.024			VA05070531	1.52
1	1	1.0	1.0	45							2.0							1.0	1.0			B363419	146.30	147.83	0.039			VA05070531	1.53
0																						B363420	147.83	149.35	0.015			VA05070531	1.52
2	6	1.0	1.5	45		0.5	Q/S	3			50.0		10.0					10.0				B363421	149.35	150.88	0.096			VA05070531	1.53
2	6	1.0	1.5	45		0.5	Q/S	3			50.0		10.0					10.0				B363422	149.35	150.88	0.039	DUP		VA05070531	
1	1	0.5	0.5	30							0.1		0.1									B363423	150.88	152.40	0.014			VA05070531	1.52
7	1	2.0	9.0	45		1.0	q/s	4			2.0	1.0	1.0						1.0			B363424	152.40	153.92	0.023			VA05070461	1.52
5	1	3.0	9.0	45		2.0	s/chl	5		0.1	3.0	0.1	2.0						1.0			B363425	153.92	155.45	0.065			VA05070461	1.53
8	1	3.0	9.0	45		1.0	q/s	5			2.0	0.1	1.0						1.0			B363426	155.45	156.97	0.058			VA05070461	1.52
1	6	0.5	0.5	45		3.0	s	5		70.0								30.0											
9	1	3.5	12.5	45		2.0	s/q	4			2.0	0.1										B363427	156.97	158.50	0.218			VA05070461	1.53
15	1	4.0	23.0	45		1.0	q/s	5			1.0	0.1					0.1		0.1			B363428	158.50	160.10	0.112		trace Mo	VA05070461	1.60
15	1	4.0	23.0	45		1.0	q/s	5			1.0	0.1					0.1		0.1			B363429	158.50	160.10	0.098	PD/CA		VA05070461	1.60
																						B363430	STANDARD 5E		1.645	5E		VA05070461	
5	1	1.0	2.5	45		1.0	s/q	4		0.1	1.0											B363431	161.10	161.54	0.026			VA05070461	0.44
7	1	1.0	3.0	45		1.0	q				1.0		0.1									B363432	161.54	163.07	1.836			VA05070461	1.53
4	1	1.0	4.0	45	30	2.0	s/q	4			2.0		0.1									B363433	163.07	164.59	0.831			VA05070461	1.52
1	1	3.0	3.0	30		6.0	s/chl	5		7.0	10.0	1.0	1.0									B363434	164.59	164.90	2.55			VA05070461	0.31
0																						B363435	164.90	165.49	0.008			VA05070461	0.59
																						B363436	BLANK		<0.005			VA05070461	
0																						B363437	165.49	166.32	0.035			VA05070461	0.83
1	1	1.5	1.5	60						4.0												B363438	166.32	167.64	0.199			VA05070461	1.32
1	3	1.0	1.0	5																									
0																						B363439	167.64	169.16	0.057			VA05070461	1.52
1	1	1.0	1.0	45							2.0											B363440	169.16	170.69	0.02			VA05070461	1.53
1	1	1.0	1.0	45																		B363441	170.69	172.21	0.054			VA05070461	1.52
1	6	0.3	0.3	45						30.0	20.0		2.0									B363442	170.69	172.21	0.082	DUP		VA05070461	1.52
3	1	1.0	1.0	45							2.0											B363443	172.21	173.74	0.025			VA05070461	1.53
3	1	1.0	1.0	45							2.0											B363444	173.74	175.26	0.062			VA05070461	1.52
1	1	7.0	7.0	50		0.5	s	3		3.0	1.0		4.0					1.0	1.0			B363445	175.26	176.78	0.203			VA05070461	1.52
0																						B363446	176.78	178.31	0.012			VA05070461	1.53
1	1	2.0	3.0	30		1.0	q	4			5.0		2.0									B363447	178.31	179.83	0.046			VA05070461	1.52
3	1	1.0	3.0	45							2.0											B363448	179.83	181.36	0.015			VA05070461	1.53
3	1	1.0	3.0	45							2.0											B363449	179.83	181.36	0.016	PD/CA		VA05070461	1.53
																						B363450	STANDARD 2B		3.12	2B		VA05070461	
4	1	2.5	7.0	45							10.0		5.0									B363451	181.36	182.88	2.38			VA05070461	1.52
2	6	0.5	1.0	45		1.0	s/q	5			40.0		10.0						5.0										

DRILL LOG LEGEND - P1	DATE: July 26th to 30th, 2006	PAGE 7 of 12	
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		191.04	195.07	Core is altered to a creamy pale green color; Sharp contact between unaltered and altered core at 45° TCA; Irregular veins of K-spar (creamy peach color) are abundant throughout (mostly mm-scale but up to 1cm); Core is speckled with anhedral to subhedral K-spar grains throughout; Along fracture and slip faces, darker green (chlorite altered?) pyrite commonly associated with fractures (v.f.gr. blebs) and smeared on faces; Pyrite in fractures found with grey clay matrix (ox'd sulphides); Sericite alteration is dominant throughout; Quartz veining is minimal; Fracturing at 193.25m = face at 50° with slickenlines at 60°; At 194.1m = Face at 10° with slickenlines at 60°.						
10		195.07	212.20	Grey GND with minor carbonate filled fractures; Local sericite alteration around fractures; At 199.64m = Rounded MSED clasts (rounded by drill), most likely cavings; At 209 - 209.25m = Intensely altered to green clay with quartz eyes; Pyrite common on slip faces (+ graphite?); Fractures at 195.8m = Fracture foliation at 30° with slickenlines at 40° TCA; At 198.0m = Fract fol'n at 65° with Slickinlines at 65°; At 205.11m = Fract fol'n at 30° with slickinlines at 30° TCA.		1			1	
11		121.20	216.87	Dark grey GND; Fine grained and softer than previous grey GND; Appears unaltered; At 212.67m - 212.70m = Intrusion of biotite poor GND (felsic?) with sharp contacts at 60°; Qtz veining is minimal (no vein >1cm); Fracturing common with chloritic (?) slickenlines; Sharp contact with felsic GND at 60°; Fractures: at 213.4m = Fracture foliation at 20° with slickenlines at 30°; At 213.88m = Fract fol'n at 45° with 50° lines; At 216.46m = Fract fol'n at 60° with lines at 70°.		1			2	
10		216.87	229.92	Grey GND with moderate to low quartz veining; Locally core is sericite altered (mod) up to 50cm; Low carbonate alteration also occurs (up to 50cm) giving core a lighter appearance and making it softer; Pyrite often occurs smeared on slip faces with chlorite; Where GND is slightly carbonate altered, quartz veining is very minimal; At 221.19m = sulphide vein with pyrrhotite and biotite with slight chlorite alteration (0.5cm); Fracture faces (foliation) with slickenlines: At 219.80m = 60°/70°; At 223.13m = 10°/30°; At 224.24m = 50°/50°; At 229.02m = 45°/45°.		2			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL																				
										Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
4	1	2.0	6.0	45						5.0	1.0		1.0									B363452	182.88	184.40	**0.16**			VA05070461	1.52
1	6	0.5	0.5	45						20.0								50.0												
0	1	1.5	6.0	45							2.0											B363453	184.40	185.93	**0.104**			VA05070461	1.53
3	1	1.0	3.0	45						0.1	1.0											B363454	185.93	187.45	**0.058**			VA05070461	1.52
6	1	1.5	5.0	45		0.4	q	4			3.0											B363455	187.45	188.98	**0.103**			VA05070461	1.53
																						B363456	BLANK		**<0.005**			VA05070461	
5	1	2.0	5.0	45							2.0		0.1									B363457	188.98	190.50	**0.074**			VA05070461	1.52
1	6	1.0	1.0	45		1.0	q	4			50.0		10.0																
1	1	2.0	2.0	45		0.5	q	3			1.0											B363458	190.50	191.04	**0.053**			VA05070461	0.54
3	1	1.0	2.5	45							1.0											B363459	191.04	192.02	**0.018**			VA05070461	0.98
1	1	1.0	1.0	45						0.1												B363460	192.02	193.55	**0.011**			VA05070461	1.53
2	1	1.0	2.0	45							0.1											B363461	193.55	195.07	**0.033**			VA05070461	1.52
2	1	1.0	2.0	45							0.1											B363462	193.55	195.07	**0.028**	DUP		VA05070461	1.52
3	1	1.0	2.5	45		1.0	q	4		1.0	1.0											B363463	195.07	196.60	**0.059**			VA05070461	1.53
5	1	2.0	4.5	45							5.0	0.1										B363464	196.60	198.12	**0.063**			VA05070461	1.52
1	1	1.0	1.0	45							1.0											B363465	198.12	199.64	**0.03**		2cm vein wi 25% pyrrho	VA05070461	1.52
2	1	2.0	4.0	45							1.0											B363466	199.64	201.17	**0.026**			VA05070461	1.53
2	1	1.5	25.0	45							1.0											B363467	201.17	202.69	**0.012**			VA05070461	1.52
2	1	2.0	3.0	45							1.0	0.1										B363468	202.69	204.22	**0.44**			VA05070461	1.53
2	1	2.0	3.0	45							1.0	0.1										B363469	202.69	204.22	**0.036**	PD/CA		VA05070461	1.53
																						B363470	STANDARD 3C		**0.092**	3C		VA05070461	
0																						B363471	204.22	205.74	**0.017**			VA05070461	1.52
2	1	1.0	1.5	45						1.0	2.0											B363472	205.74	207.26	**0.048**			VA05070461	1.52
2	6	0.3	0.6	45						80.0												B363473	207.26	208.79	**0.024**			VA05070461	1.53
																						B363474	208.79	209.30	**0.229**			VA05070461	0.51
																						B363475	209.30	209.72	**0.054**			VA05070461	0.42
																						B363476	BLANK		**<0.005**			VA05070461	
3	1	2.0	5.0			1.0	s	4		1.0	1.0											B363477	209.72	210.45	**0.152**			VA05070461	0.73
1	6	0.7	0.7							70.0								10.0												
3	1	1.0	3.0	45	60	0.2	q	4			1.0		1.0									B363478	210.45	212.21	**0.026**			VA05070461	1.76
2	1	1.0	1.5	30	60																	B363479	212.21	213.36	**0.347**			VA05070461	1.15
1	1	0.8	0.8	45						1.0	2.0											B363480	213.36	214.88	**0.035**			VA05070461	1.52
1	6	0.5	0.5	45							50.0											B363481	214.88	216.41	**0.006**			VA05070461	1.53
1	6	0.5	0.5	45							50.0											B363482	214.88	216.41	**0.019**	DUP		VA05070461	1.53
2	1	0.3	0.5	45						1.0	1.0											B363483	216.41	216.87	**0.023**			VA05070461	0.46
3	1	2.0	4.0	45	1					5.0												B363484	216.87	217.93	**0.547**			VA05070461	1.06
1	4	2.0	2.0	45																										
4	1	2.0	5.0	45		1.0	q/chl	4		0.1	2.0											B363485	217.93	219.46	**0.108**			VA05070461	1.53
1	1	1.0	1.0	45							0.1											B363486	219.46	220.98	**0.015**			VA05070461	1.52
5	1	1.5	6.0	45	60						2.0											B363487	220.98	222.50	**0.046**			VA05070461	1.52
1	6	0.5	0.5	135							40.0									50.0										
2	1	2.0	4.0	50							2.0											B363488	222.50	224.03	**0.073**			VA05070461	1.53
1	4	2.0	2.0	45																										
2	1	2.0	4.0	50							2.0											B363489	222.50	224.03	**0.047**	PD/CA		VA05070461	1.53
1	4	2.0	2.0	45																										
																						B363490	STANDARD 5E		**1.5**	5E		VA05070461	
1	1	0.5	0.5	45							2.0											B363491	224.03	225.55	**0.037**			VA05070461	1.52
2	1	3.0	4.0	45						1.0	2.0		0.1									B363492	225.55	227.08	**0.088**			VA05070461	1.53

DRILL LOG LEGEND - P1	DATE: July 26th to 30th, 2006	PAGE 9 of 12	
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.65	250.50	Green GND; Interval displays varying degrees of alteration from intense and crumbly core (234.93 - 236.22m); Carbonate veinlets +/- blebs are common throughout interval and locally caused minor alteration; Carbonate has creamy appearance; Near 3cm v.f.gr. aspy (dirty) vn are euhedral aspy grains (3x5mm); Pyrite common on slip faces - slip parallel to quartz veins have pyrite smeared along vein of slip face.		4			1	
10		250.50	266.70	Back into grey unaltered GND (locally very slightly carbonate altered - up to 20cm); Core is slightly more felsic in places; Quartz veining in minimal-moderate; Core is moderately fractured.					1	
10		266.70	277.18	Abundant sericite alteration due to fracturing in GND: Low amount of quartz veining; One large quartz vein at 272.17m (7cm); Also minor carbonate alteration and fracture filling throughout; Intense sericite alteration (crumbly) from 276.5 - 277.18m; Slickenlines are present at 270.5m at 65°; At 273.71m at 80° TCA.		4			1	
10		277.18	292.10	Mostly unaltered grey GND; Local intervals of slightly sericite and carbonate altered GND; Slight color change for sericite alteration; Slickenlines: at 277.37m = 60°; At 281.8m = 45°; At 288.86m = 10°.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Pelpgrass

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
3	1	4.0	7.0	45	0	0.5	q	5			1.0											B363493	227.08	228.60	0.337			VA05070461	1.52
3	1	1.0	2.0	45	10	0.2	q	5			2.0											B363494	228.60	229.92	0.033			VA05070461	1.32
0																						B363495	229.92	231.65	0.101			VA05070461	1.73
																						B363496	BLANK		0.049			VA05070461	
2	6	3.0	3.2	45		2.0	q/chl	5		1.0	10.0		90.0					10.0				B363497	231.65	233.17	<0.005			VA05070461	1.52
1	1	0.5	0.5	45							2.0																		
1	1	0.3	0.3	45									1.0									B363498	233.17	234.92	0.062			VA05070461	1.75
0																						B363499	234.92	236.22	0.045			VA05070461	1.30
2	4	0.4	0.7	30																		B363500	236.22	237.74	0.051			VA05070461	1.52
1	1	0.4	0.4	45							1.0							1.0											
2	1	1.5	2.0	60		0.2	q	5										1.0				B363501	237.74	239.27	0.032			VA05070461	1.53
2	4	1.0	1.5	30														1.0											
2	1	1.5	2.0	60		0.2	q	5										1.0				B363502	237.74	239.27	0.028	DUP		VA05070461	1.53
2	4	1.0	1.5	30														1.0											
2	1	0.5	1.0	45																		B363503	239.27	240.79	0.015			VA05070461	1.52
0																						B363504	240.79	241.69	0.076			VA05070461	0.90
3	1	4.0	10.0	60						2.0												B363505	241.69	242.32	0.084			VA05070461	0.63
1	1	0.5	0.5	60							1.0							1.0				B363506	242.32	243.84	0.026			VA05070461	1.52
3	1	1.0	2.0	45							2.0											B363507	243.84	245.36	0.033			VA05070461	1.52
1	1	1.0	1.0	45							1.0											B363508	245.36	246.89	0.019			VA05070461	1.53
																						B363509	245.36	246.89	0.015	PD/CA		VA05070461	1.53
																						B363510	STANDARD 4D		0.427	4D		VA05070461	
2	1	3.0	3.5	45	60	2.0	q/chl	5			0.1											B363511	246.89	248.32	0.029			VA05070461	1.43
1	4	0.5	0.5	70														1.0											
0																						B363512	248.32	248.90	0.031			VA05070461	0.58
4	1	3.0	6.0	45		5.0	5	5		1.0	1.0											B363513	248.90	250.50	0.047			VA05070461	1.60
0																						B363514	250.50	251.46	0.007			VA05070461	0.96
5	1	1.0	4.0	60	45	0.3	1	5			1.0							2.0	1.0			B363515	251.46	252.98	0.017			VA05070461	1.52
																						B363516	BLANK		<0.005			VA05070461	
0																						B363517	252.98	254.51	0.009			VA05070461	1.53
2	1	11.0	12.0	45						0.1	0.1											B363518	254.51	256.03	0.098			VA05070461	1.52
2	1	1.0	2.0	45		0.1	q	5			2.0											B363519	256.03	257.56	0.017			VA05070461	1.53
3	1	1.0	1.7	60	45	0.4	q	5		1.0	2.0	0.1	0.1									B363520	257.56	259.08	0.072			VA05070461	1.52
1	1	1.0	1.0	45							10.0								1.0			B363521	259.08	260.60	0.067			VA05070461	1.52
1	1	1.0	1.0	45							10.0								1.0			B363522	259.08	260.60	0.037	DUP		VA05070461	1.52
0																						B363523	260.60	262.13	0.041			VA05070461	1.53
2	1	1.5	1.8								1.0		1.0				0.1					B363524	262.13	263.65	0.025		Trace Mo	VA05070461	1.52
0																						B363525	263.65	265.18	0.035			VA05070461	1.53
2	1	0.5	1.0	45							1.0											B363526	265.18	266.70	0.043			VA05070461	1.52
2	1	2.5	3.0	45		0.3	q	5			1.0											B363527	266.70	268.22	0.336			VA05070461	1.52
1	6	0.2	0.2	45									90.0					5.0											
1	1	0.8	0.8	45							1.0											B363528	268.22	269.75	0.019			VA05070461	1.53
																						B365968	268.22	269.75	0.019	DP_ORIG	Old: B363528		1.53
																						B365969	268.22	269.75	0.018	PD	Old: B363529		
5	1	1.0	2.2	45							2.0		1.0				0.1					B365970	STANDARD 1A		0.978	1A	Old: B363530 Trace Mo		
2	1	7.0	7.5	45							0.1		0.1									B365971	269.75	271.40	0.025		Old: B363531		1.65
0																						B365972	271.40	272.24	0.064		Old: B363532		0.84
0																						B365973	272.24	273.81	0.034		Old: B363533	VA05070461	1.57
																						B363534	273.81	274.91	0.016				
1	1	0.5	0.5	45							0.1											B363535	274.91	276.35	0.011			VA05070461	1.44
																						B363536	BLANK		<0.005			VA05070461	
0																						B363537	276.35	277.18	0.013			VA05070461	0.83
2	1	0.5	0.8	45	60						2.0							1.0				B363538	277.18	278.98	0.005			VA05070461	1.80
4	1	2.0	5.0	45	60						2.0							2.0				B363539	278.98	280.42	0.012			VA05070461	1.44
0																						B363540	280.42	281.94	0.04			VA05070461	1.52
3	1	2.0	3.0	45							2.0		1.0						1.0			B363541	281.94	283.46	0.018			VA05070461	1.52

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		292.10	294.14	GND: Intense sericite alteration; Minimal quartz veining; Highly fractured; Slickenlines at 60° at 294.1m		5				
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	4	0.5	1.0	45																									
3	1	2.0	3.0	45							2.0		1.0						1.0			B363542	281.94	283.46	**0.009**	DUP		VA05070461	1.52
2	4	0.5	1.0	45																									
1	4	0.5	0.5	45																		B363543	283.46	284.99	**0.015**			VA05070461	1.53
1	1	0.5	0.5	30							2.0											B363544	284.99	286.51	**0.011**			VA05070461	1.52
1	1	0.5	0.5	30						2.0	10.0											B363545	286.51	288.04	**1.375**			VA05070461	1.53
1	3	0.5	0.5	30							2.0																		
1	1	0.5	0.5	45							1.0											B363546	288.04	289.56	**0.013**			VA05070461	1.52
4	1	0.6	1.5	45							3.0											B363547	289.56	291.08	**0.028**			VA05070461	1.52
1	1	0.6	0.6	45							2.0							2.0				B363548	291.08	292.10	**0.122**			VA05070461	1.02
																						B363549	291.08	292.10	**0.104**	PD/CA		VA05070461	1.02
																						B363550	STANDARD 1A		**3.31**	1A		VA05070461	
2	3	0.5	1.0	45	30								2.0						2.0			B363551	292.10	293.37	**0.012**			VA05070461	1.27
1	1	1.0	1.0	30		1.0	chl	3			4.0											B363552	293.37	294.14	**0.051**			VA05070461	0.77

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-300C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 959m

BEARING: 000 | DIP: -50°

DATE STARTED: 27-Jul-05 | DATE COMPLETED: 31-Jul-05

COORD SYSTEM: NAD 27: EASTING: 459560 NORTHING: 7099188

COORD SYSTEM: NAD 83: EASTING: 459441 NORTHING: 7099373

NAD 27 (CORRECTED for historic grid): EASTING: 459530 NORTHING: 7099198

LOGGED BY: Kevin Piepgrass

SECTION LINE(historic grid): 459525 E

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 7.92m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B363553 - B363623

Requisition #: MASP448STRGOL.05Q | Date Shipped: 19-Aug-05

Lab Record #: VA05072072 | Date Received: 25-Aug-05

Sample Sequence: B363624-B363742

Requisition #: MASP448STRGOL.05Q | Date Shipped: 26-Aug-05

Lab Record #: VA05074728 | Date Received: 1-Sep-05

Sample Sequence: B363743 - B363772

Requisition #: MASP448STRGOL.05Q | Date Shipped: 29-Aug-05

Lab Record #: VA05074737 | Date Received: 2-Sep-05

Duplicates:	363563; 363583; 363602; 363622; 363642; 363662; 363682; 363702; 363722; 363742; 363762
Preparation Duplicate/ Check Assay:	363569; 363589; 363609; 363629; 363649; 363669; 363689; 363709; 363729; 363749; 363769
Standards:	363570 (5E); 363590 (3C); 363610 (6F); 363630 (2B); 363650 (6F); 363670 (5E); 363690 (6F); 363710 (4D); 363730 (1A); 363750 (6F); 363770 (3C)
Blanks:	363556; 363576; 363596; 363616; 363636; 363656; 363676; 363696; 363716; 363736; 363756

FROM	TO	LITHOLOGY
0.00	7.92	Casing
7.92	246.89	GND (with intervals of MGD)

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	335.20	-50.20	1.20	2.20
121.92	329.50	-50.80	355.50	356.50
246.89	337.50	-51.50	3.50	4.50

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: August 14-20th 2005	PAGE 1 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 4.88	0.00	4.88	Casing - no recovery						
10	4.88 - 68.86	4.88	38.24	GND: GND is highly fractured and broken up with limonite on all surfaces; Oxidations is also present throughout GND; Locally competent core (up to 21cm pieces) at 30.68m; 95% of core is too broken up to recover vein info; Generally low recovery throughout interval; Possible fault gouge at end of interval (37.5 - 37.8m) made up of limonitic clay, very crumbly; Slickensides present at 24.45m at 45° TCA, at 34.95m at 45° TCA.	4					
10		38.24	51.00	GND is extremely oxidized; Oxidation appears to be large selvages (up to 20cm); Small - 2cm selvages also present; Oxidation selvages are also carbonate altered; Possible sericite alteration in less oxidized core (rusty green color); Core moderately broken up; Only minor quartz veining; Completely oxidized sulphide veins are present at 55m; FAULT GOUGE present from 46.95 - 47.35m, Sharp contact with oxidized GND with slickenlines at 85° TCA; Slickenlines at 49.8m at 70° TCA.	5					
10		51.00	58.84	GND is oxidized to a much lesser degree - only present along fractures and locally minor oxidation throughout, also small (1cm) weak limonite selvages; 40cm interval of highly fracture core (3x3x3 cm pieces - average); Quartz veining still low; Core switch because slightly softer and paler GND to Grey GND (~1m intervals) with sharp contacts; Sulphides in quartz veins have been leached out, leaving vugs (52.07m); Slickensides: at 55.55m = 70° TCA.	3					

DRILL LOG LEGEND P2		Date: August 14-20th, 2005	PAGE 2 of 12
Selvages	**Ox. State**	LOGGED BY: K Piepgrass	
0 = No Alteration	0 = No Oxidized Sulphides		
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																									
						Selvages				Sulphides										Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B363553	4.88	6.10	0.013			VA05072072	1.22
0																						B363554	6.10	7.67	0.009			VA05072072	1.57
1	1	0.3	0.3	45														3.0				B363555	7.67	9.14	0.045			VA05072072	1.47
																						B363556	BLANK		<0.005			VA05072072	
0																						B363557	9.14	10.67	0.009			VA05072072	1.53
0																						B363558	10.67	12.14	0.027			VA05072072	1.47
0																						B363559	12.14	13.72	0.025			VA05072072	1.58
0																						B363560	13.72	15.24	0.041			VA05072072	1.52
0																						B363561	15.24	16.76	0.018			VA05072072	1.52
0																						B363562	15.24	16.76	0.027	DUP		VA05072072	1.52
0																						B363563	16.76	19.81	0.038			VA05072072	3.05
0																						B363564	19.81	21.34	0.008			VA05072072	1.53
1	1	0.5	0.5	45														2.0				B363565	21.34	22.86	0.018			VA05072072	1.52
0																						B363566	22.86	24.38	0.031			VA05072072	1.52
0																						B363567	24.38	25.91	0.046			VA05072072	1.53
0																						B363568	25.91	27.43	0.056			VA05072072	1.52
0																						B363569	25.91	27.43	0.059	PD/CA		VA05072072	1.52
																						B363570	STANDARD 5E		1.445	5E		VA05072072	
0																						B363571	27.43	28.96	0.016			VA05072072	1.53
0																						B363572	28.96	30.48	0.089			VA05072072	1.52
0																						B363573	30.48	32.00	0.169			VA05072072	1.52
0																						B363574	32.00	33.53	0.028			VA05072072	1.53
1	1	1.0	1.0	35														5.0				B363575	33.53	35.05	0.047			VA05072072	1.52
																						B363576	BLANK		<0.005			VA05072072	
0																						B363577	35.05	36.58	0.026			VA05072072	1.53
2	1	0.5	1.0	60								0.1						10.0				B363578	36.58	38.10	0.016			VA05072072	1.52
																						B363579	38.10	39.62	0.036			VA05072072	1.52
0																						B363580	39.62	41.15	0.093			VA05072072	1.53
0																						B363581	41.15	42.67	0.738			VA05072072	1.52
0																						B363582	41.15	42.67	0.014	DUP		VA05072072	1.52
0																						B363583	42.67	44.20	0.132			VA05072072	1.53
1	1	0.4	0.4	60														10.0				B363584	44.20	45.72	0.280			VA05072072	1.52
0																						B363585	45.72	46.95	0.031			VA05072072	1.23
0																						B363586	46.95	47.35	0.146			VA05072072	0.40
2	1	0.4	0.8	40		2.0	s/q	5	4	2.0								5.0				B363587	47.35	48.77	0.027			VA05072072	1.42
1	4	0.4	0.4	50																									
2	6	0.4	0.8	60						5.0								95.0				B363588	48.77	50.29	0.099			VA05072072	1.52
2	6	0.4	0.8	60						5.0								95.0				B363589	48.77	50.29	0.097	PD/CA		VA05072072	1.52
																						B363590	STANDARD 3C		0.086	3C		VA05072072	
0																						B363591	50.29	51.00	0.035			VA05072072	0.71
0																						B363592	51.00	51.82	0.295			VA05072072	0.82
1	1	1.0	1.0	50						0.1								20.0				B363593	51.82	53.35	0.206			VA05072072	1.53
0																						B363594	53.35	54.86	0.037			VA05072072	1.51
1	1	1.0	1.0	25						1.0			2.0					50.0				B363595	54.86	56.39	0.058			VA05072072	1.53
																						B363596	BLANK		<0.005			VA05072072	
1	1	0.5	0.5	50														10.0				B363597	56.39	57.91	0.068			VA05072072	1.52
0																						B363598	57.91	58.84	0.086			VA05072072	0.93

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 3 of 12	
DRILL HOLE # : **DG05-300C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		58.84	61.33	GND: Back to very limonitic GND with overprinted sericite +/- chlorite alteration within oxidized selvages; Sulphide vein at 59.83m contains 50% fresh, fine grained pyrite; Fresh fine grained euhedral pyrite inside vugs (up to 0.2x0.4cm vugs) of quartz veins are present.	5					
10		61.33	64.01	GND: Back into less oxidized GND with limonite on fractures as previously described; Vuggy quartz veins still present with limonite staining inside and fresh euhedral fine grained pyrite.						
10		64.01	68.86	GND: Highly fractured with intervals up to 30cm of competent core; Limonite on/in carbonate lined fractures and opened faces; GND appears slightly more mafic here (?); Quartz veins contain vugs (5x3x4mm); Slickenlines: at 64.01m = 70° TCA; At 66.23m = 60° TCA.	3					
30	68.86 - 74.08	68.86	74.08	GND: GND has higher percentage of biotite, giving it a much darker appearance (mafic?); Minor quartz veining; Large quartz veins have sericite alteration selvages; From 68.86m - 69.52m = intense sericite alteration with large 5x6cm blebs of quartz with carbonate fractures; From 71.0 - 71.5m = Highly fractured MGD (3.5 x 5 x 2 cm avg) with calcite and some limonite on fractures; Slickenlines: at 70.11m = 60° TCA; At 73.35m = 30° TCA.		1				
10	74.08 - 80.92	74.08	80.92	Grey GND with no apparent alteration; Local carbonate alteration from 75.90 - 76.23m; Majority of quartz veins have quartz selvages; MGD interval with sharp contact from 77.02 - 77.16m at 30° TCA; Pyrite common in carbonate fracture filling.					1	
30	80.92 - 88.39	80.92	88.39	MGD (More mafic GND): Back into MGD as prev. description; Quartz veins commonly have quartz flooded selvages; Frequent carbonate fracture filling; Slickenlines: at 84.15m = 45°; At 81.37m = 45° TCA.						
10	88.39 - 91.62	88.39	91.62	GND: Has been altered to a greyish green colour (sericite) to a deeper green color (chlorite?); Chlorite altered GND is much softer and is crumbly whereas ser altered GND is much more competent (retained silica); Carbonate fracture filling is abundant throughout; Quartz veining is minimal, but tends to be thicker (~4cm) with low sulphide content.		5	5	1		
10		91.62	93.96	GND: GND is light in color with high carbonate content = carbonate alteration; Interval is very crumbly; High k-spar content (cream color); K-spar is very soft; Minimal quartz veining with sericite/chlorite selvages (~1m) slickenlines present on broken core.		2		2	4	2
30		93.96	99.49	MGD: Back into MGD as seen in 66.86 - 74.08m; Quartz veining is more abundant; Carbonate fracture filling abundant; Core moderately broken up.						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration, 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: August 14-20th, 2005

LOGGED BY: K Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.4	0.6	50		2.0	q/s	5	3	2.0												B363599	58.84	59.94	**0.165**			VA05072072	1.10
1	6	0.4	0.4	60		3.0	q/s	5	3	50.0																			
3	1	0.5	1.5	60	45					2.0			3.0					5.0				B363600	59.94	61.33	**0.210**			VA05072072	1.39
0																						B363601	61.33	62.58	**0.031**			VA05072072	1.25
0																						B363602	61.33	62.58	**0.033**	DUP		VA05072072	1.25
1	1	0.5	0.5	60									2.0					5.0				B363603	62.58	64.01	**0.253**			VA05072072	1.43
2	1	0.3	0.5	30	60	0.5	1	5			2.0		3.0									B363604	64.01	65.53	**0.190**			VA05072072	1.52
2	1	1.0	1.5	40	60					2.0	1.0		2.0					5.0				B363605	65.53	67.06	**0.105**			VA05072072	1.53
3	1	1.0	2.2	45						1.0			1.0					2.0				B363606	67.06	68.86	**0.048**			VA05072072	1.80
4	1	1.0	4.0	45	60	5.0	s	5		2.0	2.0		2.0					5.0				B363607	68.86	70.10	**0.460**			VA05072072	1.24
3	1	1.0	25.0	30																		B363608	70.10	71.63	**0.033**			VA05072072	1.53
3	1	1.0	25.0	30																		B363609	70.10	71.63	**0.024**	PD/CA		VA05072072	1.53
																						B363610	STANDARD 6F		**2.730**	6F		VA05072072	
1	1	0.6	0.6	45						1.0												B363611	71.63	73.15	**0.025**			VA05072072	1.52
2	1	2.0	2.5	45		4.0	s/cb				4.0								2.0			B363612	73.15	74.08	**0.072**			VA05072072	0.93
7	1	1.6	3.3	30	50	0.5	q	5			2.0							1.0				B363613	74.08	75.90	**0.515**			VA05072072	1.82
1	3	0.5	0.5	60																		B363614	75.90	76.23	**0.077**			VA05072072	0.33
7	1	1.0	4.5	45	60	0.4	q	s			5.0	1.0	2.0									B363615	76.23	77.72	**0.125**			VA05072072	1.49
																						B363616	BLANK		**<0.005**			VA05072072	
4	1	0.5	2.0	45	60	0.4	q	5			5.0		1.0									B363617	77.72	79.25	**0.231**			VA05072072	1.53
2	1	0.5	0.9	45	55	0.3	q	s			25.0											B363618	79.25	80.92	**0.114**			VA05072072	1.67
1	3	1.0	1.0	45		0.2	q	5			50.0											B363619	80.92	82.30	**0.064**			VA05072072	1.38
1	6	0.2	0.2	45						1.0	1.0																		
8	1	2.0	6.0	45	60	1.5	s	5		1.0	2.0	1.0										B363620	82.30	83.82	**0.263**			VA05072072	1.52
2	1	0.5	1.0	45							2.0											B363621	83.82	85.34	**0.091**			VA05072072	1.52
1	5	0.4	0.4	30																									
2	1	0.5	1.0	45							2.0											B363622	83.82	85.34	**0.116**	DUP		VA05072072	1.52
1	5	0.4	0.4	30																									
4	1	1.0	2.5	60	30						2.0											B363623	85.34	86.87	**0.299**			VA05072072	1.53
1	6	0.2	0.2	45							50.0																		
4	1	1.0	3.0	45							2.0											B363624	86.87	88.39	**0.199**			VA05074728	1.52
2	1	4.0	5.0	45									0.1									B363625	88.39	89.86	**0.178**			VA05074728	1.47
0																						B363626	89.86	90.38	**0.113**			VA05074728	0.52
1	1	4.0	4.0	45		29.0	chl	5		2.0	1.0		0.1									B363627	90.38	91.10	**0.085**			VA05074728	0.72
1	1	1.0	1.0	45						1.0	1.0		1.0									B363628	91.10	91.62	**0.197**			VA05074728	0.52
1	1	1.0	1.0	45						1.0	1.0		1.0									B363629	91.10	91.62	**0.112**	PD/CA		VA05074728	0.52
																						B363630	STANDARD 2B		**3.210**	2B		VA05074728	
2	1	1.0	1.5	45		0.5	s/chl	4		1.0	2.0		3.0									B363631	91.62	92.96	**0.174**			VA05074728	1.34
3	1	1.0	2.0	45		0.5	s/chl	4			2.0		0.1									B363632	92.96	93.96	**0.229**			VA05074728	1.00
1	5	0.5	0.5	30						1.0	1.0																		
4	1	1.0	2.5	45	8						1.0											B363633	93.96	95.40	**0.382**			VA05074728	1.44
3	1	2.0	3.0	45		1.0	s/chl	4		1.0	5.0	1.0	1.0									B363634	95.40	96.86	**0.185**			VA05074728	1.46
1	1	1.0	1.0	30																		B363635	96.86	98.08	**0.152**			VA05074728	1.22
																						B363636	BLANK		**0.013**			VA05074728	
1	1	1.0	1.0	40																		B363637	98.08	99.49	**0.222**			VA05074728	1.41

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 5 of 12	
DRILL HOLE # : **DG05-300C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		99.49	105.65	GND: GND has become very felsic; MDG/GND contact distinct but crumbly; higher carbonate and k-spar content; Creamy k-spar is harder than interval 91.62 - 93.96m; Carbonate fracture filling has pale green hue (sericite); Quartz veining tends to be irregular +/- displaced or in blebs with carbonate fractures; Core is relatively soft; Slickenlines: at 99.69m on 10° face, lines at 10° TCA; At 102.0m on 20° face, lines at 85°; At 103.83m on 60° face, lines at 70° TCA; At 102.51m, on 0° face, lines at 70° TCA.		2	1	3	2	
10		105.65	124.97	GND: GND slightly darker (greyer) than previous (99.49 - 105.65m); Less abundant carbonate fractures; Less abundant k-spar; GND is also harder and less broken-up; Local sericite alteration (intensive) from 110.65m - 111.49m (largest interval), sharp contact with quartz vein at 45°; Local intensive carbonate alteration 106.76 - 106.97m and 109.92 - 110.14m; Quartz veining tends to be more abundant in sericite altered veins; <2mm qtz/chl/sulphide (po) veins are common; Chlorite + carb common on slip face with smeared pyrite; Slickenlines: at 113.3m on 30° face, lines at 60°; At 115.3m, face at 50° with lines at 50°; At 119.9m, face at 119.9m with lines at 70°; At 121.92m, face at 30° with lines at 60° TCA.		2	1	2	1	
10		124.97	147.83	GND: Grey GND; Very gradual change from previous interval (105.65 - 124.97m); GND is slightly darker; Carb and chlorite alteration are present on a majority of the fracture and slip faces - commonly with pyrite smearing; Pyrrhotite and arsenopyrite common in chl/s selvages; <1mm qtz+chl/cb/po veinlets common with quartz/ser selvages; Minor intervals of slightly more felsic (?) GND; Slickenlines: at 128.15m, face at 10° with lines at 45° TCA; At 135.8m, face at 45° with lines at 45° TCA; At 142.5m, face at 45° with lines at 60°.		2	2	2	2	

DRILL LOG LEGEND P2		Date: August 14-20th, 2005	PAGE 6 of 12
Selvages	Ox. State	LOGGED BY: K Piepgrass	
0 = No Alteration	0 = No Oxidized Sulphides		
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																	Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides									Oxidation					From	To					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
0																						B363638	99.49	100.58	0.459			VA05074728	1.09
4	1	1.5	3.0	45	60	0.5	q/chl	3			0.1		0.1									B363639	100.58	102.11	0.062			VA05074728	1.53
3	1	1.0	2.0	45	30						1.0		1.0									B363640	102.11	103.63	0.387			VA05074728	1.52
2	1	1.5	2.0	45	30	1.0	q/chl	5														B363641	103.63	104.83	0.782			VA05074728	1.20
2	1	1.5	2.0	45	30	1.0	q/chl	5														B363642	103.63	104.83	1.465	DUP		VA05074728	1.20
4	1	0.4	1.5	45	30	0.5	q/chl	3			2.0		1.0									B363643	104.83	105.65	4.910			VA05074728	0.82
3	1	0.4	1.0	30	45						2.0											B363644	105.65	106.68	0.194			VA05074728	1.03
4	1	1.0	2.2	45	30	0.3	q/chl	5			2.0		2.0									B363645	106.68	108.20	0.238			VA05074728	1.52
3	1	0.3	0.8	45	30	0.5	q/chl	5			10.0		1.0									B363646	108.20	109.73	0.328			VA05074728	1.53
0																						B363647	109.73	110.53	0.460			VA05074728	0.80
4	1	0.5	2.0	45							2.0											B363648	110.53	111.50	0.196			VA05074728	0.97
4	1	0.5	2.0	45							2.0											B363649	110.53	111.50	0.975	PD/CA		VA05074728	0.97
																						B363650	STANDARD 6F		2.820	6F		VA05074728	
1	5	0.4	0.4	30																		B363651	111.50	112.78	0.081			VA05074728	1.28
2	1	0.8	1.6	30		1.0	q/chl	4			0.1											B363652	112.78	114.30	0.126			VA05074728	1.52
6	1	1.5	4.5	45	30	2.0	q/chl	5		0.1	2.0								1.0			B363653	114.30	115.82	0.513			VA05074728	1.52
2	1	0.5	0.8	45						1.0	2.0	0.1										B363654	115.82	117.35	0.098			VA05074728	1.53
4	1	1.0	2.2	30	45	0.2	q/chl	5			1.0											B363655	117.35	118.87	0.107			VA05074728	1.52
																						B363656	BLANK		<0.005			VA05074728	
5	1	0.4	1.8	45		1.0	q/chl	4			1.0											B363657	118.87	120.40	0.294			VA05074728	1.53
2	1	0.5	1.0	30							1.0		1.0									B363658	120.40	121.92	0.151			VA05074728	1.52
2	1	0.5	0.7	30		0.3	q/chl	4			1.0											B363659	121.92	123.44	0.168			VA05074728	1.52
3	1	0.8	1.5	45		1.0	chl	3			1.0		1.0									B363660	123.44	124.97	1.860			VA05074728	1.53
4	1	0.4	1.2	45	30	1.0	s/chl	3			2.0	1.0										B363661	124.97	126.49	0.077			VA05074728	1.52
4	1	0.4	1.2	45	30	1.0	s/chl	3			2.0	1.0										B363662	124.97	126.49	0.077	DUP		VA05074728	1.52
6	1	1.0	3.0	45	30	0.5	s/chl	3			2.0		1.0									B363663	126.49	128.02	0.041			VA05074728	1.53
3	1	1.0	1.7	5	10	0.2	q/chl	5			3.0											B363664	128.02	129.55	0.177			VA05074728	1.53
3	1	0.3	0.7	45		1.0	q/chl	3			2.0											B363665	129.55	131.06	0.258			VA05074728	1.51
4	1	0.5	1.5	45		1.5	chl	5			2.0		2.0									B363666	131.06	132.54	0.111			VA05074728	1.48
3	5	0.5	1.5	45							1.0	0.1	1.0																
9	1	2.0	7.6	45		2.0	s	4		1.0	4.0	0.1	1.0									B363667	132.54	134.11	0.189			VA05074728	1.57
4	1	1.0	3.0	45		1.0	s/chl	4		0.1	2.0											B363668	134.11	135.64	0.085			VA05074728	1.53
4	1	1.0	3.0	45		1.0	s/chl	4		0.1	2.0											B363669	134.11	135.64	0.055	PD/CA		VA05074728	1.53
																						B363670	STANDARD 5E		1.490	5E		VA05074728	
6	1	1.5	4.0	45	30	1.0	s/chl	4			5.0	1.0	1.0									B363671	135.64	137.16	0.302			VA05074728	1.52
1	3	0.3	0.3	45		1.0	chl	5																					
1	5	0.4	0.4	45		1.0	chl	4					1.0																
2	1	2.0	3.5	45							2.0	1.0	0.1									B363672	137.16	138.68	0.296			VA05074728	1.52
1	5	0.2	0.2	45		0.5	chl	4																					
4	1	1.2	2.5	45							1.0		1.0									B363673	138.68	140.21	0.113			VA05074728	1.53
3	1	1.0	2.0	45		1.0	chl	4		1.0	2.0	1.0	0.1									B363674	140.21	141.73	0.188			VA05074728	1.52
5	1	1.1	3.5	45	30	0.2	q	5			3.0	1.0	0.1									B363675	141.73	143.26	0.063			VA05074728	1.53
																						B363676	BLANK		0.010			VA05074728	
2	1	1.5	1.8	45							2.0		1.0									B363677	143.26	144.76	0.045			VA05074728	1.50
2	1	0.6	1.0	45							2.0		2.0									B363678	144.76	146.18	0.077			VA05074728	1.42
1	5	0.4	0.4	45		0.3	k	5			2.0		0.1																

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 1 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		147.83	156.32	GND: Grey GND that is more heavily fractured and broken up than the previous interval (124.97 - 147.83m); Long shallow (0-30°) fractures abundant with cb/s/chl and commonly pyrite; At 153.7m = 1cm felsic granitic (very fine grained) vein at 30° TCA; Slickenlines: at 150.65m, face at 45° with lines at 50° TCA.		2	2	3	2	
10		156.32	166.24	GND: Grey GND; GND still more heavily fractured than previous interval (147.83 - 156.32m) with a general size of 4x4x3cm; Locally more competent core up to 35cm in length; Locally very crumbly sand sized; Blocks commonly have sericite +/- chlorite alteration; Fracture faces mostly have calcite with a tinge of green (pale sericite), commonly with pyrite; Slickenlines: 165.65m, face to 45° and lines at 50° TCA; At 163.37m, face at 60° with lines at 65° TCA; At 165.85m, face at 30°, lines at 45°.		2	2			
10		166.24	168.46	GND: Intensely sericite altered =/- chlorite alteration; Extremely crumbly to completely altered core; Crumbly core contains remnant quartz veins as quartz eyes aligned; Disseminated pyrite throughout; Competent core has abundant carbonate throughout; Slickenlines at 168.43m with face at 5° and lines at 70° TCA.		5	2			
10		168.46	175.00	GND: Grey GND, competent; Quartz veins tend to have large-moderate sericite selvages; No real obvious alteration in interval.						
10		175.00	189.63	GND: Majority of GND has been argillic altered; Contacts between unaltered GND and argillic altered GND tends to be sharp at about 45-60° (vein parallel?); Unaltered intervals ~60m (4 of them); Sericite selvages occur along fractures with calcite and chlorite on fractures (up to 6cm); Common to see quartz veins at edge of sericite/chlorite fracture selvages; Slickenlines: At 178.2m, face at 45° with lines at 45° TCA; At 178.7m, frac at 20° with lines at 60°; At 184.7m, face at 10° with lines at 20° TCA; At 190.25m, face at 30° with lines at 60°.				4	1	

DRILL LOG LEGEND P2		Date: August 14-20th, 2005	PAGE 3 of 12
Selvages	**Ox. State**	LOGGED BY: K Piepgrass	
0 = No Alteration	0 = No Oxidized Sulphides		
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																	Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides									Oxidation					From	To					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
1	2	0.3	0.6	45							2.0																		
7	1	1.0	3.0	45	30	0.3	k/s	5		1.0	5.0		0.1									B363679	146.18	147.83	**0.119**			VA05074728	1.65
1	3	0.3	0.3	45																									
2	5	0.3	0.6	45							2.0																		
3	1	0.3	0.8	45	30	0.2	q	5			2.0		2.0									B363680	147.83	149.35	**0.066**			VA05074728	1.52
2	1	1.5	1.8	60	30	2.0	s	5		2.0	1.0		2.0									B363681	149.35	150.88	**0.076**			VA05074728	1.53
2	1	1.5	1.8	60	30	2.0	s	5		2.0	1.0		2.0									B363682	149.35	150.88	**0.144**	DUP		VA05074728	1.53
4	1	1.0	3.0	60	45					1.0	1.0											B363683	150.88	152.40	**0.102**			VA05074728	1.52
1	3	0.2	0.2	30						0.1	0.1																		
0																						B363684	152.40	153.92	**0.139**			VA05074728	1.52
0																						B363685	153.92	155.45	**0.224**			VA05074728	1.53
4	1	0.6	2.0	45		3.0	s/cb			3.0	5.0	0.1	2.0									B363686	155.45	156.32	**0.472**			VA05074728	0.87
1	1	0.3	0.3	30																		B363687	156.32	157.62	**0.098**			VA05074728	1.30
0																						B363688	157.62	159.15	**0.094**			VA05074728	1.53
0																						B363689	157.62	159.15	**0.086**	PD/CA		VA05074728	1.53
																						B363690	STANDARD 6F		**2.680**	6F		VA05074728	-
4	1	0.6	1.8	45	30						4.0		2.0									B363691	159.15	160.02	**0.177**			VA05074728	0.87
7	1	0.6	3.0	45		0.3	cb/chl				1.0		1.0									B363692	160.02	161.54	**0.067**			VA05074728	1.52
0																						B363693	161.54	163.07	**0.287**			VA05074728	1.53
2	1	0.8	1.6	45						0.1												B363694	163.07	164.59	**0.072**			VA05074728	1.52
1	1	0.3	0.3	45							1.0		1.0									B363695	164.59	165.50	**0.181**			VA05074728	0.91
																						B363696	BLANK		**0.009**			VA05074728	
2	1	0.5	1.0	60									0.1									B363697	165.50	166.24	**0.349**			VA05074728	0.74
0																						B363698	166.24	167.61	**0.299**			VA05074728	1.37
7	1	1.6	6.0							5.0												B363699	167.61	168.46	**5.460**			VA05074728	0.85
6	1	1.0	2.6	45		5.0	s	3		2.0	3.0		2.0									B363700	168.46	169.90	**0.209**			VA05074728	1.44
3	1	0.6	1.5	45		1.0	q/s	4			2.0											B363701	169.90	170.69	**0.435**			VA05074728	0.79
3	1	0.6	1.5	45		1.0	q/s	4			2.0											B363702	169.90	170.69	**0.121**	DUP		VA05074728	0.79
3	1	1.0	2.2	45		11.0	s/cb	4			2.0		0.1									B363703	170.69	172.21	**0.099**			VA05074728	1.52
5	1	1.0	3.0	45	30	0.5	q/s	4			2.0		3.0									B363704	172.21	173.74	**0.141**			VA05074728	1.53
3	1	0.4	1.1	30	45						1.0											B363705	173.74	175.00	**0.082**			VA05074728	1.26
0																						B363706	175.00	176.23	**0.286**			VA05074728	1.23
0																						B363707	176.23	176.91	**0.027**			VA05074728	0.68
1	1	1.0	1.0	45							1.0		1.0									B363708	176.91	178.31	**0.198**			VA05074728	1.40
1	1	1.0	1.0	45							1.0		1.0									B363709	176.91	178.31	**0.190**	PD/CA		VA05074728	1.40
																						B363710	STANDARD 4D		**0.457**	4D		VA05074728	
1	1	0.5	0.5	30		3.0	s/q	3		1.0	2.0		2.0									B363711	178.31	179.83	**0.443**			VA05074728	1.52
2	6	0.2	0.4	45		0.4	q	5			25.0																		
2	1	1.0	1.6	45							1.0		1.0									B363712	179.83	181.36	**0.089**			VA05074728	1.53
1	1	0.5	0.5	45		0.3	q	5			4.0											B363713	181.36	182.88	**2.110**			VA05074728	1.52
6	1	1.5	3.0	45		0.3	q	5			2.0											B363714	182.88	184.40	**0.089**			VA05074728	1.52
1	1	0.3	0.3	45							1.0											B363715	184.40	185.33	**0.150**			VA05074728	0.93
																						B363716	BLANK		**<0.005**			VA05074728	
3	1	0.5	1.5	45							2.0											B363717	185.33	186.87	**0.134**			VA05074728	1.54
4	1	0.5	1.5	45	30	2.0	s/chl	4		1.0	2.0	0.1	2.0									B363718	186.87	188.27	**0.145**			VA05074728	1.40
3	1	0.2	0.6	45		0.2	q	4			2.0											B363719	188.27	189.63	**1.255**			VA05074728	1.36

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 4 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		189.63	219.94	GND: GND appears to have various degrees of ser/chl/arg/carb alteration; Sericite alteration is dominant throughout; Carb and clay alteration tend to occur together where core is very crumbly; Clay altered core has disseminated f g py (1-2%) throughout and mm-scale veinlets; Disseminated pyrite occurs in dark-grey clay veins; Competent core goes through color change gradually (k-spar + ser = ser = ser + chl); K-spar alteration may be overprinted by sericite alteration (soft, non reactive creamy grains); Contacts with clay/carb altered core tends to be sharp; Q V at 194.3m has euhedral pyrite (up to 2x2.2mm); In highly clay/carb/sericite altered GND large Q V are broken up with abdnt euh-subhed py; At 207.26m core white wi hint of green, grey q.v's w/in, qtz blebs abndt or area of silicification (4x8cm), cb vning abundt, ends at 208.79m; Slickenlines: at 201.0m, face at 10° wi lines at 35°; At 207.66m = 45° wi lines at 85°; At 209.75m = 45° wi lines at 75°; At 212.32m = 30° wi lines at 85°; At 216.41m = 60° wi lines at 70° TCA.		5	3	3	2	
10		219.94	231.19	GND: Grey GND; Mod - highly broken up; Chl + cb on fracture faces; Local argillic alteration with lesser carb alteration; Medium grained aspy and po present on fracture faces as well as fine grained py; Very gradually core is becoming lighter in colour and softer (argillic alteration); Large 15cm quartz vein at end of interval with a sharp contact to next interval; Slickenlines: At 222.3m, face at 45° with lines at 80° TCA; At 224.5m, face at 5° with lines at 90°; At 228.1m face at 5° with lines at 90°; At 230.2m face at 30° with lines at 45° TCA.		1		1	1	

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 10 of 12
Selvages: 0 = No Alteration; 5 = Intense Alt'n — Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass	
Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite		
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz		

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	4.0	60.0	45		2.0	s/chl	3			1.0											B363720	189.63	190.66	**0.163**			VA05074728	1.03
8	1	0.8	3.0	45	60	7.0	q/chl	5														B363721	190.66	192.02	**0.153**			VA05074728	1.36
8	1	0.8	3.0	45	60	7.0	q/chl	5														B363722	190.66	192.02	**0.360**	DUP		VA05074728	1.36
6	1	4.0	9.0	45		4.0	5	5		1.0	3.0	0.1	2.0									B363723	192.02	193.55	**1.745**			VA05074728	1.53
2	1	9.0	10.0	45						10.0	1.0		5.0									B363724	193.55	195.07	**7.650**			VA05074728	1.52
4	1	2.0	3.5	60	45					5.0			2.0									B363725	195.07	196.60	**2.490**			VA05074728	1.53
1	6	0.5	0.5	80						95.0												B363726	196.60	198.12	**0.745**			VA05074728	1.52
5	1	1.0	2.5	80	45					1.0												B363727	198.12	199.64	**0.294**			VA05074728	1.52
1	1	1.0	1.0	45						1.0			1.0									B363728	199.64	201.17	**0.188**			VA05074728	1.53
1	4	0.4	0.4	35																									
1	1	1.0	1.0	45						1.0			1.0									B363729	199.64	201.17	**0.146**	PD/CA		VA05074728	1.53
1	4	0.4	0.4	35																									
																						B363730	STANDARD 1A		**0.991**	1A		VA05074728	
2	1	2.0	2.5	45																		B363731	201.17	202.58	**0.555**			VA05074728	1.41
4	1	1.0	3.0	45	30					2.0			0.1									B363732	202.58	203.65	**0.577**			VA05074728	1.07
3	1	5.0	8.0							25.0												B363733	203.65	205.17	**1.725**		Py only in one vein	VA05074728	1.52
5	1	1.2	4.5	45							2.0		1.0									B363734	205.17	206.48	**0.477**			VA05074728	1.31
3	1	2.0	6.0	45	30					1.0	1.0		1.0									B363735	206.48	207.26	**13.350**			VA05074728	0.78
																						B363736	BLANK		**0.011**			VA05074728	
4	1	1.0	2.5	45	60																	B363737	207.26	208.79	**0.454**			VA05074728	1.53
0																						B363738	208.79	210.10	**0.357**			VA05074728	1.31
0																						B363739	210.10	211.44	**0.124**			VA05074728	1.34
0																						B363740	211.44	212.50	**1.150**			VA05074728	1.06
2	1	0.5	1.0	60						0.1	0.1		0.1									B363741	212.50	213.60	**0.514**			VA05074728	1.10
2	1	0.5	1.0	60						0.1	0.1		0.1									B363742	212.50	213.60	**0.291**	DUP		VA05074728	1.10
1	6	0.5	0.5	80						50.0												B363743	213.60	214.30	**0.116**			VA05074737	0.70
0																						B363744	214.30	216.01	**0.521**			VA05074737	1.71
0																						B363745	216.01	217.21	**0.596**			VA05074737	1.20
4	1	1.0	4.0	60							1.0	0.1	1.0									B363746	217.21	218.67	**0.790**			VA05074737	1.46
2	6	1.0	1.3	70						60.0			5.0									B363747	218.67	219.94	**0.383**			VA05074737	1.27
1	1	1.0	1.0	60						10.0			2.0																
3	1	1.0	2.0	60		0.8	k	4			2.0		2.0									B363748	219.94	220.98	**0.430**			VA05074737	1.04
3	1	1.0	2.0	60		0.8	k	4			2.0		2.0									B363749	219.94	220.98	**0.382**	PD/CA		VA05074737	1.04
																						B363750	STANDARD 6F		**2.870**	6F		VA05074737	
1	1	0.3	0.3	80		0.4	q	4														B363751	220.98	222.50	**0.392**			VA05074737	1.52
1	2	0.3	0.3	70																									
7	1	3.5	7.0	70		0.3	k	5		1.0	2.0		2.0									B363752	222.50	224.03	**0.462**			VA05074737	1.53
1	6	0.3	0.3	70																									
3	1	0.5	1.2	65		1.0	k	5			2.0		2.0									B363753	224.03	225.55	**0.744**			VA05074737	1.52
1	2	0.5	0.5	70																									
1	1	1.0	1.0	60							2.0	0.1	1.0									B363754	225.55	227.08	**0.440**			VA05074737	1.53
1	3	1.0	1.0	60							2.0																		
2	3	1.0	1.5	60		1.0	q/s	3			5.0											B363755	227.08	228.60	**0.803**			VA05074737	1.52
1	4	0.3	0.3	60																									
																						B363756	BLANK		**<0.005**			VA05074737	
5	1	1.7	6.5	50							2.0		0.1									B363757	228.60	230.12	**1.220**			VA05074737	1.52
1	2	0.5	0.5	50						2.0																			

DRILL LOG LEGEND - P1	DATE: August 14-20th 2005	PAGE 11 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.19	246.89	GND: GND gradually increasing intensity of argillic alteration down hole; Slight to moderation at top of interval to extreme at EOH; Carb alteration and fracturing prevalent throughout; Local sericite alteration associated with dark grey clay(?); Where core is most intensely altered, only clay and quartz eyes remain (213.84 - 246.89m), also fresh v f gr blebs of py disseminated throughout 1-2%; Pyrite veinlets/blebs common in increased argillic alteration; Quartz vein commonly displaced. Slickenlines: At 232.2m, face at 10° with lines at 75°; At 233.3m face at 10° with lines at 45°; At 236.1m face at 10° with lines at 45° TCA.		1		5	3	
				EOH						

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 12 of 12
Selvages 0 = No Alteration 5 = Intense Alt'n	**Ox. State** 0 = No Oxidized Sulphides 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.3	0.3	60		0.3	q	4			20.0		5.0									B363758	230.12	230.85	**0.267**			VA05074737	0.73
2	1	15.0	20.0	45						1.0			0.1									B363759	230.85	231.19	**7.420**			VA05074737	0.34
0																						B363760	231.19	232.63	**8.820**			VA05074737	1.44
2	1	0.6	0.8	70		0.5	q	5			4.0											B363761	232.63	234.48	**0.357**			VA05074737	1.85
2	1	0.6	0.8	70		0.5	q	5			4.0											B363762	232.63	234.48	**0.190**	DUP		VA05074737	1.85
6	1	1.0	2.5	75							2.0		0.1									B363763	234.48	236.16	**0.817**			VA05074737	1.68
2	6	0.5	0.7	75							25.0																		
1	1	1.0	1.0	80							2.0											B363764	236.16	237.51	**0.356**			VA05074737	1.35
4	1	15.0	37.0	45	60						1.0											B363765	237.51	239.27	**1.645**			VA05074737	1.76
1	6	0.3	0.3	70						90.0																			
0																						B363766	239.27	240.79	**1.110**			VA05074737	1.52
0																						B363767	240.79	242.32	**1.060**			VA05074737	1.53
0																						B363768	242.32	243.84	**0.870**			VA05074737	1.52
0																						B363769	242.32	243.84	**0.956**	PD/CA		VA05074737	1.52
																						B363770	STANDARD 3C		**0.095**	3C		VA05074737	
0																						B363771	243.84	245.36	**1.945**			VA05074737	1.52
0																						B363772	245.36	246.89	**0.695**			VA05074737	1.53

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-301C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 994m

BEARING: 000 | DIP: -50°

DATE STARTED: 31-Jul-05 | DATE COMPLETED: 05-Aug-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459655 NORTHING: 7099185

COORD SYSTEM: NAD 83: EASTING: 459536 NORTHING: 7099370

NAD 27 (CORRECTED for historic grid): EASTING: 459625 NORTHING: 7099195

SECTION LINE(historic grid): 459625 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 3.65m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	3.65	Casing
3.65	308.02	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B381577 - B381600 and B364201 - B364316

Requisition #: MASP448STRGOL.05Q Date Shipped: 19-Aug-05

Lab Record #: VA05072075 Date Received: 25-Aug-05

Sample Sequence: 364317 - 364457

Requisition #: MASP448STRGOL.05Q Date Shipped: 26-Aug-05

Lab Record #: VA05074726 Date Received: 2-Sept-05

Duplicates:	381582; 364202; 364222; 364242; 364262; 364282; 364302; 364322; 364342; 364362; 364382; 364402; 364422; 364442
Preparation Duplicate/ Check Assay:	381589; 364209; 364229; 364249; 364269; 364289; 364309; 364329; 364349; 364369; 364389; 364409; 364429; 36449
Standards:	381590 (2B); 364210 (5E); 364230 (1A); 364250 (4D); 364270 (7G); 364290 (3C); 364310 (1A); 364330 (6F); 364350 (4D); 364370 (5E); 364390 (2B); 364410 (7G); 364430 (4D); 364450 ( )
Blanks:	381596; 364216; 364236; 364256; 364276; 364296; 364316; 364436; 364356; 364376; 364396; 364416; 364436; 364456

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
167.6	334.9	-51.4	000.9	001.9
213.4	335.3	-49.8	001.3	002.3
243.8	336.3	-47.8	002.3	003.3
304.8	336.3	-47.9	002.3	003.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

No surveys above 167.63m due to NQ casing

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 1 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-3.65	0.00	3.65	Casing						
10	3.65-17.34	3.65	17.34	GND: 40% pervasively stained GND; Very broken up where competent, with longest core length of 19cm; Weathered to clay over 20% of section; This clay is pale whitish-yellow brown or bright orange-brown; Recovery is poor to excellent (0% - 87%); Generally corresponding to clay context (increased clay = reduced recovery); First 5 samples contain selvage-less 0.5cm quartz veins at ~60° TCA, as well as wide selvages (primarily oxidized) with no visible veinage; These selvages probably result from microfractures serving as channels for atmospheric and meteoric waters; From 12.19 - 17.34m is 90% stained pale brown, even through competent sections; Boundary between oxidized and unoxidized is clear but irregular, surrounding veinlets and veins.	3	0	0	1	1	
10		17.34	24.38	GND: 60% of section is oxidized and limonitic GND reduced to sandy/granular texture - fine to coarse. Colour is pale yellowish brown; Yellow due to oxidized carbonate (still effervesces weakly); Competent GND sections (up to 10cm long) are pervasively oxidized to pale brown, but with GND texture preserved; Fine grained, 2mm minerals (bt, feldspar) maximum diameter.	4	0	0	1	1	
10		24.38	35.05	GND: Intensely broken-up, crumbly GND; Sandy texture over 80% of section; All limonitic and ox'd; Competent core (up to 20cm long) is pale brown, ox'd with pervasive limonite; Texture preserved in only 10% of competent material rest is faulted such that the rock is aphanitic and has brecciated (angular) quartz along planar foliation at 50° (40-60°) TCA; Definitive fault material between 26.7 - 27.35m and from 32.0 - 33.0m in competent sections; Broken regularly at 70° TCA.	5	0	0	1	1	
10		35.05	48.45	GND highly weathered by closely-spaced veinlets of carbonate-rich limonitic material throughout matrix. Feldspars weathering to clay minerals. Broken-up crumbly; Veins less visible. Small veins of calcite produce carb-rich selvages/zones; Soft, opaque, dull grey, semi-metallic sulphide in quartz veins (chalcocite?) appears, <5% of vein, somewhat (~50%) weathered to chlorite/sericite; At 39.7m = quartz/k-spar vein contains increased hem (ox'd), hematite continues; Increasingly brecciated through section, last 3m contain no competent pieces larger than 10cm long; Texture is brecciated - GND chunks in crumbly clay/fine to coarse sand-size material matrix.						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 2 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages			Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
2	1	2.0	2.5	60		0.0															B381577	3.65	4.57	**0.076**		2cm vein in pieces; No selvages seen	VA05072075	0.92
1	1	3.0	3.0			3.0	q/chl	3								0.1					B381578	4.57	6.10	**1.135**		Trace Chalcocite (?); Pieces of vein and selvage	VA05072075	1.53
1	1	0.5	0.5	55		0.0			0.0												B381579	6.10	7.62	**0.026**		Selvages seen but no vein.	VA05072075	1.52
				60	120	6.0	q/chl	2																				
4	2	0.5	1.6	0	50	1.0	q/k	2													B381580	7.62	9.14	**0.060**			VA05072075	1.52
1	1	0.4	0.4	70		0.0										3.0										Trace Chalcocite		
2	2	1.0	1.0	55		1.0	q/k	1	3												B381581	9.14	10.67	**0.045**			VA05072075	1.53
1	1	1.0	1.0	20					0.1																			
2	2	1.0	1.0	55		1.0	q/k	1	3												B381582	9.14	10.67	**0.037**	DUP		VA05072075	1.53
1	1	1.0	1.0	20					0.1																			
6	1	2.0	6.0	60		2.0	q/k	4	3	0.1						2.0					B381583	10.67	12.19	**0.048**			VA05072075	1.52
1	1	0.4	0.4	55												0.1					B381584	12.19	13.72	**0.055**		Trace moly (?)	VA05072075	1.53
																						13.72	15.24			No recovery; Clay seam	VA05072075	1.52
0																					B381585	15.24	16.76	**0.040**			VA05072075	1.52
0																					B381586	16.76	17.34	**0.036**			VA05072075	0.58
0																					B381587	17.34	18.29	**0.052**			VA05072075	0.95
0																					B381588	18.29	19.81	**0.038**			VA05072075	1.52
0																					B381589	18.29	19.81	**0.039**	PD/CA		VA05072075	1.52
																					B381590	STANDARD 2B		**2.880**	2B		VA05072075	
0																					B381591	19.81	21.34	**0.050**			VA05072075	1.53
1	1	0.6	0.6	50		1.0	q/k	3	2	0.0											B381592	21.34	22.86	**0.059**			VA05072075	1.52
0																					B381593	22.86	24.38	**0.068**			VA05072075	1.52
2	1	0.5	0.7	20		2.0	q/k	3	2	0.0											B381594	24.38	25.91	**0.087**			VA05072075	1.53
0																					B381595	25.91	27.43	**0.093**			VA05072075	1.52
																					B381596	BLANK		**<0.005**			VA05072075	
0																					B381597	27.43	28.96	**0.136**			VA05072075	1.53
0																					B381598	28.96	30.48	**0.091**			VA05072075	1.52
0																					B381599	30.48	32.00	**0.189**			VA05072075	1.52
0																					B381600	32.00	33.53	**0.310**			VA05072075	1.53
0																					B364201	33.53	35.05	**0.020**		New book	VA05072075	1.52
0																					B364202	33.53	35.05	**0.028**	DUP		VA05072075	1.52
0																					B364203	35.05	36.58	**0.031**			VA05072075	1.53
1	2	0.6	0.6	50		2.0	q/k	2	2												B364204	36.58	38.10	**0.044**			VA05072075	1.52
2	1	2.0	3.0	50		0.5	q/k/cb	2	2												B364205	38.10	39.62	**0.039**			VA05072075	1.52
2	2	1.0	1.5	60	10	0.5	cb/k	3	2							2.0												
3	2	1.0	2.0	50		1.0	cb/k	4	3												B364206	39.62	41.15	**0.111**			VA05072075	1.53
4	1	0.8	3.0	70	50	2.0	cb/q	3	3												B364207	41.15	42.67	**0.087**			VA05072075	1.52
1	1	1.0	1.0	70		1.0	q	1	5												B364208	42.67	44.20	**0.032**			VA05072075	1.53
1	1	1.0	1.0	70		1.0	q	1	5												B364209	42.67	44.20	**0.033**	PD/CA		VA05072075	1.53
																					B364210	STANDARD 5E		**1.490**	5E		VA05072075	
2	1	1.0	2.0	50		2.0	q	1	3												B364211	44.20	45.72	**0.045**		Oxidized hematite; brecciated quartz	VA05072075	1.52
2	3	1.5	2.5	60		5.0	cb	3	5																			

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005 PAGE 3 of 16											
DRILL HOLE # : DG05-301C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered								**Carbonate** 0 = No Effervescence 5 = Strong Effervescence		
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)							
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
10		48.45	56.88	FAULT ZONE. GND texture reduced to 1mm-grain size; coherent core 50% of section, shows re-arranged, brecciated fine grained GND; Considerably weakened/weathered along veinlets of carb-rich limonite in irregular orientations approximately 5 veinlets/square cm.	4	1	1	2	2			
10		56.88	75.53	GND: Typical GND texture re-appears, with fewer, but still prevalent limonite coated veins, causing intense breakage. Selvages around limonite veinlets are visible here (again) - irregular in width, up to 2cm; Moderate slickenslides on fracture faces at 20° TCA; Biotite, limonite, feldspar; 15cm silicified zone at 70.6m, broken at 30°-60° TCA.	3	0	1	1	1			
10		75.53	76.76	GND/FLT: Small zone of extreme weathering and aphanitic texture; FAULT ZONE: Brecciated-gouge for 20cm from 76.40 - 76.6m; General trend of shear is at 40° TCA; Veins are in first 30cm of sample	4	2	1	2	2			
10		76.76	89.07	GND; similar to 35.05-48.45m: Limonitic veinlets through matrix, weathering feldspars; Zones of intense shear noted; At 82.1 - 82.5m = Gouge/brecciated quartz/GND; At 84.25 - 84.85m = Clay gouge (30cm) and brecciated GND - shear to 130° OR 50°, At 87.42m - 88.35m = 90% clay, 10% brecciated GND and quartz. Strong shear to 30° TCA; At 79.3m = small sulphide vein (oxidized pyrite and aspy) parallels 1cm quartz vein; At 74.2m is an angular, 2cm xenolith of basalt which may contain sulphides (black, semi-metallic). From 83.82m - 84.18m is a zone of relatively unaltered GND; Calcite and limonite concentrated into veins/veinlets (8) at 160° TCA. This interval of coherent core is followed by 60cm of clay gouge and brecciated rock, heavily oxidized (noted above as zone of intense shear). At 87.42m, a 93cm zone of intense shear contains 2 quartz veins, slightly brecciated and probably re-oriented into shear direction.	4	0	0	2	2			
10		89.07	97.54	GND: Gradational zone between heavily limonized rock (entire hole to here) and white clay mineral/carb-rich GND with preserved texture (med-grained GND); Slickenslides visible in sericite/carbonate on fractures at <20° TCA; Diss aspy ~1 % of GND.	2	1	1	0	1			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 4 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							chl/q	1																				
1	3	1.0	1.0	80		6.0	cb	3	4													B364212	45.72	47.24	0.030			VA05072075	1.52
4	1	1.2	4.0	40	50	2.0	q/k	1	3													B364213	47.24	48.45	0.149			VA05072075	1.21
1	1	1.0	1.0	65																		B364214	48.45	49.39	0.025		Brecciated Quartz	VA05072075	0.94
1	1	0.6	0.6	60		0.5	q/cb	2	3													B364215	49.39	50.29	0.055			VA05072075	0.90
																						B364216	BLANK		<0.005			VA05072075	
0																						B364217	50.29	51.82	0.044			VA05072075	1.53
3	1	1.2	3.2	60		0.0				5.0							0.1	1.0				B364218	51.82	53.34	1.160		Trace moly	VA05072075	1.52
1	1	1.0	1.0	50																		B364219	53.34	54.86	0.079		Gradational Boundaries	VA05072075	1.52
3	4	2.0	4.0	160	145	0.0																B364220	54.86	56.39	0.083			VA05072075	1.53
2	1	1.0	2.0	50		4.0	q/cb	3	2	0.1								5.0										
2	1	1.0	2.0	50		4.0	q/cb	1	3	2.0								5.0				B364221	56.39	56.88	0.054			VA05072075	0.49
2	1	1.0	2.0	50		4.0	q/cb	1	3	2.0								5.0				B364222	56.39	56.88	0.052	DUP		VA05072075	0.49
3	1	1.0	3.0	65		0.5	q/cb	2	2	3.0							0.1	5.0				B364223	56.88	57.91	0.053		Trace moly	VA05072075	1.03
2	1	1.0	2.0	40	70	2.0	q/cb	1	3	2.0								5.0				B364224	57.91	59.44	0.099		~10% hem	VA05072075	1.53
5	1	1.0	5.0	50		0.0							4.0					3.0				B364225	59.44	60.96	0.234			VA05072075	1.52
3	1	2.2	4.5	50		4.0	q/k/cb	2	2													B364226	60.96	62.48	0.080			VA05072075	1.52
4	1	0.8	3.0	50	60	1.5	q/cb/k	3	1		0.1									3.0		B364227	62.48	64.01	0.117			VA05072075	1.53
2	1	1.5	2.0	2		1.0	q/k/cb	2	2													B364228	64.01	65.53	0.046			VA05072075	1.52
2	1	1.5	2.0	2		1.0	q/k/cb	2	2													B364229	64.01	65.53	0.057	PD/CA		VA05072075	1.52
																						B364230	STANDARD 1A		0.843	1A		VA05072075	
0																						B364231	65.53	67.06	0.056			VA05072075	1.53
2	1	1.0	2.0	50		1.0	q/k	3	3				2.0						4.0			B364232	67.06	68.58	0.082			VA05072075	1.52
1	1	2.0	2.0	5		1.0	q/cb	2	3	1.0			0.1					5.0				B364233	68.58	70.10	0.066			VA05072075	1.52
0																						B364234	70.10	71.63	0.035			VA05072075	1.53
2	1	1.0	1.5	60	35	1.0	q/cb	2	2	1.0					1.0			5.0				B364235	71.63	73.15	0.094			VA05072075	1.52
																						B364236	BLANK		<0.005			VA05072075	
2	1	0.6	1.2	30	60	2.0	q	2	4				1.0									B364237	73.15	74.68	0.111			VA05072075	1.53
1	1	1.0	1.0	50		2.0	q	2	4	0.1								5.0				B364238	74.68	75.53	0.166			VA05072075	0.85
1	6	0.4	0.4	50		1.0	q	3	2	40.0			20.0					4.0											
3	1	1.0	2.0	45	20	0.0				2.0					0.1			5.0				B364239	75.53	76.76	0.270			VA05072075	1.23
3	3	0.5	1.5	50		1.0	q/cb	2	3	5.0		0.1	0.1		2.0			3.0				B364240	76.76	77.72	0.207			VA05072075	0.96
2	1	1.0	2.0	50		0.0				0.1								5.0				B364241	77.72	79.25	0.067			VA05072075	1.53
2	1	1.0	2.0	50		0.0				0.1								5.0				B364242	77.72	79.25	0.098	DUP		VA05072075	1.53
5	1	1.0	4.0	50	70	1.0	q	3	2	1.0			5.0		1.0			5.0	4.0			B364243	79.25	80.77	0.088			VA05072075	1.52
1	6	0.3	0.3	60		0.5	q	4	0	30.0			20.0					5.0											
2	1	1.0	1.7	70		0.0				0.1			0.1					5.0				B364244	80.77	82.30	0.023			VA05072075	1.53
5	1	1.5	5.5	40	50	2.0	q/cb	3	3	3.0	1.0							5.0				B364245	82.30	83.82	0.086			VA05072075	1.52
2	1	2.0	3.0	70	45						6.0		3.0					1.0	3.0			B364246	83.82	85.34	0.114			VA05072075	1.52
1	4	0.3	0.3	160		0.0				0.0																			
3	1	1.5	3.0	60		1.0	q/cb	3	3	1.0			1.0		5.0			5.0				B364247	85.34	86.87	0.105			VA05072075	1.53
2	1	2.0	4.0	30	60	0.0				1.0								5.0				B364248	86.87	88.39	0.126		Brecciated quartz in shear zone	VA05072075	1.52
1	1	2.0	4.0	30	60	0.0				1.0								5.0				B364249	86.87	88.39	0.107	PD/CA		VA05072075	1.52
																						B364250	STANDARD 4D		0.336	4D		VA05072075	
2	1	0.3	0.6	45		2.0	q/cb	4	1	3.0			1.0	0.1				4.0	3.0			B364251	88.39	89.07	0.036		Grey quartz	VA05072075	0.68
3	1	1.0	3.0	30		1.0	q/cb	2	1						2.0			5.0				B364252	89.07	90.42	0.073			VA05072075	1.35
4	1	1.0	3.0	35	60	8.0	q/cb	2	2	1.0			8.0					5.0				B364253	90.42	91.44	0.094		Massive aspy	VA05072075	1.02
							cb/chl	3																				

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 5 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		97.54	112.78	GND: Virtually no limonite staining left. GND is still soft and very broken up due to carbonate weathering. Competent core up to 24cm long in section. 80% is crumbly and less than 10cm long, not complete diameter due to <10° TCA pervasive fractures. Slickenslides in quartz/carb vein at 104.3m expressed in oxidized pyrite; Fracture plane at 10° TCA (rough surface). Sample from 104.51 - 105.16m contains many quartz veins, some crosscutting at 25° and 75° TCA; Veins at 75° appear later, po concentrated at intersection (1cm grain). Also veins at 50° TCA contain ~15% py and some cpy and py. Crosscutting veins again at 109.2m; Large (4cm) quartz vein with <1mm oxidized pyrite overprinted by small, 0.5cm wide quartz veins containing po concentrated at intersections with edge of larger vein.	1	1	1	3	4	
10		112.78	116.47	GND: Clay gouge zone with clayey oxidized sulphide lenses; Fabric/lenses are at 50-80° TCA. Brecciated GND and qtz (<2cm in diameter) make up ~30% of section. 70% of the grain sizes are 1-2mm and smaller. Sericitic and carbonate-rich; Color is pale beige to dark grey.	2	4	2	4	4	
10		116.47	128.02	GND: Coherent carb-rich core with 20% GND texture still present. Sulphide veins and veinlets pervade - ~5 per metre. Sometimes these veinlets are just partial, pinched out at lenses. No selvage info noted because alteration covers the entire section, as noted on this page.	2	3	1	3	4	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 6 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages																							
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.0	3.0	50	60	2.0	q/cb	1	2				3.0					2.0				B364254	91.44	92.96	**0.054**		Massive aspy in massive black mineralization (py?)	VA05072075	1.52
1	4	0.2	0.2	70		2.0	q/cb	2	3																				
8	1	1.0	6.0	60		2.0	q/chl	2	0		2.0				0.1							B364255	92.96	94.49	**0.146**			VA05072075	1.53
																						B364256	BLANK		**<0.005**			VA05072075	
4	1	1.0	3.0	60		0.0					4.0				1.0							B364257	94.49	96.01	**0.028**			VA05072075	1.52
3	1	1.0	3.0	70		1.0	q	1	0		0.1		0.1		1.0							B364258	96.01	97.54	**0.573**			VA05072075	1.53
4	1	1.0	3.5	70		2.0	q	1	0		1.0		0.1			0.1						B364259	97.54	99.06	**0.080**			VA05072075	1.52
2	1	20.0	22.0	80		0.0				3.0	2.0		1.0					5.0				B364260	99.06	100.58	**0.049**		Vein contains ~20% calcite	VA05072075	1.52
2	3	9.0	11.0	40		6.0	cb/chl	3	1	3.0								4.0				B364261	100.58	102.11	**0.108**			VA05072075	1.53
3	1	1.0	3.0	60						3.0	2.0		2.0					4.0											
2	3	9.0	11.0	40		6.0	cb/chl	3	1	3.0								4.0				B364262	100.58	102.11	**0.083**	DUP		VA05072075	1.53
3	1	1.0	3.0	60						3.0	2.0		2.0					4.0											
5	1	1.0	5.0	60		1.0	q/chl	3	0	2.0	7.0	1.0	4.0					1.0				B364263	102.11	103.63	**0.068**		Pieces	VA05072075	1.52
1	3	2.0	2.0			6.0	cb/chl	3		1.0					0.1			5.0											
2	6	0.3	0.5	60		1.0	q/cb	3	1		####											B364264	103.63	104.51	**0.104**		Irregular Edges	VA05072075	0.88
3	1	2.0	4.0	60	80	1.0	q	2	0		5.0	1.0						4.0											
1	3	10.0	10.0			0.0				5.0	1.0							4.0											
9	1	1.5	7.5	25	75	2.0	q/cb	4	0		15.0	3.0	1.0									B364265	104.51	105.16	**0.157**			VA05072075	0.65
3	3	4.0	8.0	60		2.0	cb/chl	4	0	6.0			0.1		1.0			5.0				B364266	105.16	106.68	**0.209**		Aspy disseminated in selvage	VA05072075	1.52
1	6	1.0	1.0	60		8.0	cb/chl	5			80.0	4.0	1.0																
2	3	2.0	4.0	80		6.0	cb/chl	3	1	1.0								5.0				B364267	106.68	108.20	**0.311**		Irregular edges - angle?	VA05072075	1.52
3	1	3.0	5.0	60	45	8.0	cb/chl	3	0	5.0	5.0							5.0				B364268	108.20	109.73	**0.076**			VA05072075	1.53
1	3	0.4	0.4	65		2.0	cb/chl	3	0																				
3	1	3.0	5.0	60	45	8.0	cb/chl	3	0	5.0	5.0							5.0				B364269	108.20	109.73	**0.090**	PD/CA		VA05072075	1.53
1	3	0.4	0.4	65		2.0	cb/chl	3	0																				
																						B364270	STANDARD 7G		**4.320**	7G		VA05072075	
3	1	2.0	4.0	40	60	6.0	q	3	0	5.0					2.0			5.0				B364271	109.73	111.25	**0.093**		Massive aspy and py in separate veinlets	VA05072075	1.52
3	6	1.0	1.6	50	70	20.0	q/chl	4	1	50.0			60.0					3.0											
							s/cb	1																					
5	1	1.0	5.0	50		6.0	s/q/chl	4	1	5.0	2.0							5.0				B364272	111.25	112.78	**0.073**			VA05072075	1.53
2	3	0.8	1.3	50		4.0	q/chl	4	0	10.0								5.0									Oxidized py clay at margins of vein		
							cb																						
1	1	1.5	1.5	55						5.0								5.0				B364273	112.78	114.30	**0.319**			VA05072075	1.52
3	6	25.0	60.0	40						100.0								5.0									Clay gouge with py		
3	6	4.0	10.0	75	45					100.0								5.0				B364274	114.30	115.82	**0.312**			VA05072075	1.52
1	6	1.0	1.0	75						100.0												B364275	115.82	116.47	**0.067**			VA05072075	0.65
																						B364276	BLANK		**<0.005**			VA05072075	
3	1	2.0	4.0	55						10.0								4.0				B364277	116.47	117.35	**0.369**			VA05072075	0.88
3	6	1.0	2.0	70	80					100.0								5.0											
5	1	9.0	19.0	45						8.0			5.0					4.0				B364278	117.35	118.87	**1.890**			VA05072075	1.52
4	6	4.0	8.5	45	80					100.0								3.0											
6	6	0.2	1.0	60	50					100.0								5.0				B364279	118.87	119.62	**0.369**			VA05072075	0.75
1	1	0.6	0.6	25						2.0								5.0											
1	1	5.0	5.0	45						15.0								4.0				B364280	119.62	120.40	**0.709**			VA05072075	0.78
3	6	0.5	1.1		25					10.0								5.0				B364281	120.40	121.92	**0.246**			VA05072075	1.52
4	1	1.5	3.0	35	60					5.0	10.0							3.0											
3	6	0.5	1.1		25					10.0								5.0				B364282	120.40	121.92	**0.444**	DUP		VA05072075	1.52

DRILL LOG LEGEND - P1

DATE: Aug 14 - 20, 2005 PAGE 7 of 16

DRILL HOLE # :
DG05-301C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		128.02	140.11	GND: Beginning of visible selvages around qtz/sulphide veins, so 40% of section is unaltered. Veinlets of oxidized sulphides are common, only veins >2mm are recorded on second page, but veinlets are ~20/metre. Sulphide vein at 138.15m is branching into surrounding rock and pyrite (60% ox'd) appears disseminated into irregular veinlets for 20cm surrounding vein. Sheared-out GND with carb and sulphide-rich clays from 139.05 - 139.60m.						
10		140.11	144.78	GND: In addition to selvages surrounding qtz and sulphide veins, separated by unaltered GND: This section also contains zones of carbonate-rich clay gouge (2): from 140.2 - 141.22m and 143.56 - 143.8m. In these zones GND texture is 'smeared' out into a trend at 10-35° TCA. Slickenslides (minor) noted on low angle fracture faces (rough).	1	2	2	2	3	
10		144.78	155.44	GND: 80% unaltered GND. Competent core with excellent recovery. Selvages visible on infrequent qtz,carb and qtz/carb veins. One large qtz vein from 149.77m to 150.60m contains small chunks of altered GND; sericitic alteration at margins. Slickensides (minor) in calcite on rough, low-angle fracture faces. Change from HQ to NQ at 151.33m; Crumbly carb-infused section from 154.0m to 155.3m (last sample).	0	2	1	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
4	1	1.5	3.0	35	60					5.0	10.0							3.0											
4	1	1.5	4.0	50						20.0								2.0				B364283	121.92	123.44	**0.316**			VA05072075	1.52
1	6	1.0	1.0	45	65					100.0								5.0											
5	1	3.0	6.0	35	65					10.0	0.1							4.0				B364284	123.44	124.97	**0.363**			VA05072075	1.53
3	6	0.2	0.6	45	35					60.0								5.0											
2	1	0.5	1.0	70						5.0	0.1							5.0				B364285	124.97	126.49	**0.333**			VA05072075	1.52
3	6	0.5	0.9	30	160					60.0								5.0											
1	1	3.0	3.0	35						10.0								3.0				B364286	126.49	128.02	**0.242**			VA05072075	1.53
5	6	0.3	1.5							100.0								5.0											
8	1	2.0	9.0	40	70						5.0							2.0				B364287	128.02	129.54	**0.297**			VA05072075	1.52
5	1	3.0	10.0	30	70	2.0	q/cb	3	0		5.0	0.1										B364288	129.54	131.06	**0.617**			VA05072075	1.52
1	3	7.0	7.0	30		0.0				0.1								5.0											
5	1	3.0	10.0	30	70	2.0	q/cb	3	0		5.0	0.1										B364289	129.54	131.06	**0.496**	PD/CA		VA05072075	1.52
1	3	7.0	7.0	30		0.0				0.1								5.0											
																						B364290	STANDARD 3C		**0.092**	3C		VA05072075	
2	1	2.0	3.0	55							2.0											B364291	131.06	132.59	**0.893**			VA05072075	1.53
1	3	1.0	1.0	40						10.0	2.0							5.0											
3	1	3.0	5.0	70-		8.0	cb/chl	4	1	10.0	20.0							4.0				B364292	132.59	133.47	**1.320**			VA05072075	0.88
4	6	0.4	0.9	65	40	10.0	cb/chl	5	1	80.0								5.0											
3	1	0.6	1.2	60		20.0	cb/chl	5	1													B364293	133.47	134.11	**0.099**			VA05072075	0.64
3	1	1.5	4.0	40	60					5.0	3.0							1.0				B364294	134.11	134.89	**1.180**			VA05072075	0.78
2	6	1.0	1.3	60						60.0								5.0											
5	1	2	3.5	60.0		8	cb/chl	4	1	5								5.0				B364295	134.89	135.64	**1.575**			VA05072075	0.75
2	6	0.3	0.6	60		12.0	cb/chl	5	1	80.0								3.0											
																						B364296	BLANK		**<0.006**			VA05072075	
3	1	1.5	3.0	60		30.0	cb/chl	4	1	2.0	2.0							5.0				B364297	135.64	136.41	**0.327**			VA05072075	0.77
2	4	2.0	3.0	30	60	30.0	cb/chl	5	1	4.0								5.0											
4	1	0.5	2.0	40	90	1.0	q	3	0		5.0											B364298	136.41	137.16	**0.029**			VA05072075	0.75
3	4	0.3	0.9	70	35	20.0	cb/chl	3																					
2	4	1.0	1.2	50	70	30.0	cb/chl	5	0	0.0												B364299	137.16	137.93	**0.073**			VA05072075	0.77
2	6	1.0	1.0	790		20.0	cb/chl	5	0	90.0								5.0											
5	1	1.0	3.0	30		20.0	cb/chl	4	1	5.0	0.1	0.1	0.1					2.0				B364300	137.93	138.68	**0.937**			VA05072075	0.75
2	6	3.0	3.3	30		25.0	cb/chl	5	3	100.0								3.0											
6	1	1.0	5.0	70	40	15.0	q.cb	4	0		10.0											B364301	138.68	140.11	**1.315**			VA05072075	1.43
6	1	1.0	5.0	70	40	15.0	q.cb	4	0		10.0											B364302	138.68	140.11	**3.330**	DUP		VA05072075	1.43
4	6	0.4	1.0	70		10.0	cb/chl	5	1	100.0								5.0				B364303	140.11	141.19	**0.269**			VA05072075	1.08
2	6	1.0	2.0	35		20.0	cb/chl	4	2	100.0																			
							chl	1																					
4	1	1.0	4.0	50	100	0.0																B364304	141.19	141.73	**0.739**			VA05072075	0.54
1	4	0.5	0.5	30		0.0																							
4	1	1.0	4.0	50		2.0	q/cb	3	0	10.0												B364305	141.73	143.26	**0.296**			VA05072075	1.53
3	1	1.0	2.5	40	100	6.0	q/chl	3	1		0.1											B364306	143.26	144.78	**0.146**			VA05072075	1.52
3	4	0.3	0.9	40		3.0	q/cb	3	1	20.0								4.0											
3	3	0.5	1.5	60	30	24.0	cb/chl	3		20.0	2.0						3.0	5.0				B364307	144.78	146.30	**0.084**		Moly in selvages	VA05072075	1.52
3	1	1.0	2.5	50		8.0	q/chl	3	0	1.0	3.0	5.0										B364308	146.30	147.83	**1.706**			VA05072075	1.53
3	4	0.3	0.8	50		10.0	cb/chl	4	1	40.0								5.0											
3	1	1.0	2.5	50		8.0	q/chl	3	0	1.0	3.0	5.0										B364309	146.30	147.83	**1.775**	PD/CA		VA05072075	1.53
3	4	0.3	0.8	50		10.0	cb/chl	4	1	40.0								5.0											
																						B364310	STANDARD 1A		**0.810**	1A		VA05072075	
2	1	1.0	2.0	60		2.0	q/chl	2	1		10.0											B364311	147.83	149.35	**1.415**			VA05072075	1.52
2	1	1.0	2.0	60		2.0	q/chl	4	0																				
3	1	83.0	85.0	45		4.0	q/a	5		0.1	0.1		0.1									B364312	149.35	150.88	**0.134**			VA05072075	1.53
							cb/chl	2	1																				
2	1	2.0	4.0	80		10.0	q	3		4.0							0.1	1.0				B364313	150.88	152.41	**0.091**			VA05072075	1.53
2	1	0.5	1.0	75	15	0.5	q/cb	3	0													B364314	152.41	155.44	**0.065**		Error; 3m sample	VA05072075	3.03
1	3	1.0	1.0	45		3.0	q/chl	2	0																				

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 9 of 16	
DRILL HOLE # : DG05-301C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		155.44	162.36	GND: Predominantly (90%) altered GND with chlorite and carbonate, minor sericite. Zone of many sulphide veinlets/few <1cm veins, approx 3 per m. Competent core, but softened to clay-rich in selvages surrounding sulphide veins. Oxidation of pyrite and carbonate.	1	2	3	1	2	
10		162.36	165.84	Larger qtz veinlets within still-competent GND. Sulphide veins continue with clay'd, oxidized pyrite, to a maximum alteration selvage of 50cm. Still, due to decreased number of veins and veinlets, more unaltered GND is present (50%).	1	2	2	0	1	
10		165.84	169.71	Carbonate-infused GND. Crumbly and soft, makes veins/veinlets difficult to see.	1	1	1	3	3	
10		169.71	181.50	GND: Unaltered, with quartz veins with small selvages; 60% of these veins have straight edges and clear selvages; 40% have gradational/irregular boundaries with little to no selvages.	0	1	1	0	1	
10		181.50	184.54	GND: 95% powdery/crumbly carb-infused GND.	0	1	0	2	4	
10		184.54	191.07	GND: Coherent core, but highly altered with chlorite, sericite and carb; Carb appears in veins and veinlets, generally at 50° TCA; as well as in ~2mm grains in selvages (alt'd feldspar); GND here appears finer-grained and sheared toward the end of the section. Slickenslides on fracture faces at moderate angles TCA (20-50°). Perfect cubic pyrite (1.2mm) at 188.66m.	1	2	3	0	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
2	6	0.6	1.1	45		40.0	q/cb/chl	4	1	100.0								5.0				B364315	155.44	156.97	**0.572**			VA05072075	1.53
1	1	1.5	1.5	50		1.0	q	2		2.0			0.1					3.0											
																						B364316	BLANK		**<0.005**			VA05072075	
3	1	1.0	2.0	70		5.0	q/chl	4	1	2.0	0.1		4.0					3.0				B364317	156.97	158.50	**0.286**			VA05074726	1.53
3	6	0.3	0.9	60		12.0	q/cb/chl	5	1	100.0								4.0											
2	1	1.5	2.0	70		2.0	cb/s	3	1		10.0	0.1										B364318	158.50	160.02	**0.156**		Clay selvage	VA05074726	1.52
2	6	0.3	0.6	55		40.0	cb/chl	5	1	100.0								4.0											
2	1	1.0	2.0	50		2.0	q/cb/chl	3	0	5.0	5.0							4.0				B364319	160.02	161.55	**0.085**		Oxidized py, not po	VA05074726	1.53
1	3	1.0	1.0	80		10.0	cb/chl	5	0	0.0																			
1	6	1.0	1.0	70		50.0	cb/chl	5	0	100.0								5.0											
2	1	1.0	2.0	70	80	6.0	cb/chl	3			5.0							1.0				B364320	161.55	162.36	**0.808**		20% clay	VA05074726	0.81
3	6	0.5	1.5	80	35	40.0	q/s	3	1	100.0								5.0											
							cb/chl	2																					
1	1	1.5	1.5	50		6.0	q/chl	3			4.0	1.0										B364321	162.36	163.07	**0.145**			VA05074726	0.71
1	1	1.5	1.5	50		6.0	q/chl	3			4.0	1.0										B364322	162.36	163.07	**0.144**	DUP		VA05074726	0.71
1	3	0.8	0.8	45		4.0	q/cb/chl	3	0		20.0											B364323	163.07	164.60	**0.293**		Oxidized calcite	VA05074726	1.53
4	1	3.5	8.5	60		16.0	cb/chl	3	1	8.0								2.0											
1	6	0.3	0.3	50		12.0	cb/s	4	1	100.0								4.0											
1	1	1.0	1.0	50		8.0	q/cb/chl	3	0	10.0								1.0				B364324	164.60	165.84	**1.325**			VA05074726	1.24
1	3	1.0	1.0	155		10.0	q/cb/s	4	1	8.0								5.0											
0																						B364325	165.84	166.75	**0.428**			VA05074726	0.91
2	1	1.5	3.0	70		2.0	q/cb	3	0		5.0							4.0				B364326	166.75	168.06	**0.584**		Pale po	VA05074726	1.31
2	1	0.5	1.0	50	35	1.0	q/cb	3			2.0											B364327	168.06	169.16	**0.168**		Pyrite concentrated at edges	VA05074726	1.10
1	4	0.5	0.5	30		0.4	cb/chl	1	0	5.0								5.0											
2	1	1.0	2.0	50		4.0	q/cb	3	0		0.1							5.0				B364328	169.16	169.71	**0.201**			VA05074726	0.55
2	1	1.0	2.0	50		4.0	q/cb	3	0		0.1							5.0				B364329	169.16	169.71	**0.196**	PD/CA		VA05074726	0.55
																						B364330	STANDARD 6F		**2.62**	6F		VA05074726	
3	1	1.0	3.0	80	50	2.0	q/chl	1	0		20.0	1.0	2.0									B364331	169.71	170.68	**0.23**			VA05074726	0.97
4	1	1.5	4.0	55		1.0	q/chl	3		3.0			0.1					5.0				B364332	170.68	172.21	**0.102**			VA05074726	1.53
2	3	1.0	2.0	50		6.0	q/cb	3	1	10.0	0.1																		
3	1	6.0	8.0	50	70	10.0	q/cb/chl	3	0	4.0	20.0											B364333	172.21	173.73	**1.685**			VA05074726	1.52
2	6	0.8	1.3	40		3.0	q/cb	4	1	20.0	50.0							0.0											
4	1	1.5	35.0	50	60	1.0	q	3			2.0											B364334	173.73	175.26	**0.066**			VA05074726	1.53
3	1	1.2	2.0	50		2.0	q	3			2.0							2.0				B364335	175.26	176.20	**0.297**			VA05074726	0.94
																						B364336	BLANK		**<0.005**			VA05074726	
3	1	1.0	2.0	80	50	3.0	q/cb/s	3	0	0.1	3.0							1.0				B364337	176.20	177.12	**0.019**			VA05074726	0.92
4	1	2.0	4.5	50		3.0	q/cb/s	3	0		1.0	0.1										B364338	177.12	178.44	**0.212**			VA05074726	1.32
1	6	1.0	1.0	65		6.0	q/cb/s	5	0		60.0							1.0											
4	1	1.0	3.0	70		4.0	q/cb/s	5			5.0											B364339	178.44	179.98	**0.405**			VA05074726	1.54
3	1	2.5	5.5	50	35	2.0	q/cb/s	4			2.0							1.0				B364340	179.98	181.50	**0.345**			VA05074726	1.52
2	6	0.4	0.8	50		15.0	cb/chl	5		60.0								5.0											
1	1	1.0	1.0	55		2.0	q/cb/s	2	1		0.1											B364341	181.50	183.02	**0.429**			VA05074726	1.52
2	6	0.5	1.0	15		4.0	cb/chl	3		80.0								5.0											
1	1	1.0	1.0	55		2.0	q/cb/s	2	1		0.1											B364342	181.50	183.02	**0.592**	DUP		VA05074726	1.52
2	6	0.5	1.0	15		4.0	cb/chl	3		80.0								5.0											
3	1	1.5	4.5	60		2.0	q/cb/s	3	1	0.1								5.0				B364343	183.02	184.54	**1.155**			VA05074726	1.52
4	1	1.5	3.3	50		6.0	q/s	3	0	0.1			0.1					5.0				B364344	184.54	185.84	**1.11**			VA05074726	1.30
3	6	0.5	1.4	35		30.0	cb/chl	5	1	90.0				0.1															
1	1	1.0	1.0	60		3.0	q/cb/s	2	0		4.0							1.0				B364345	185.84	186.43	**0.275**			VA05074726	0.59
5	1	0.8	2.8	40	60	2.0	q/cb/s	4	0							0.1						B364346	186.43	187.45	**0.957**			VA05074726	1.02
3	6	1.0	2.5	40		40.0	cb/chl/s	5			80.0							3.0											
4	1	1.2	4.0	40	55	4.0	q/s/chl/cb	4	1	15.0	5.0							1.0				B364347	187.45	188.67	**0.16**			VA05074726	1.22
1	3	2.0	2.0	55		10.0	chl/cb	4	0	1.0								5.0											
1	6	1.0	1.0	60		6.0	q	2	0	100.0								3.0											
2	1	1.0	2.0	15						0.1								5.0				B364348	188.67	189.88	**0.129**			VA05074726	1.21
2	1	1.0	2.0	15						0.1								5.0				B364349	188.67	189.88	**0.126**	PD/CA		VA05074726	1.21
																						B364350	STANDARD 4D		**0.42**	4D		VA05074726	

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 11 of 16	
DRILL HOLE # : DG05-301C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		191.07	196.23	GND: Unaltered GND with a few quartz veins and sulphide veinlets; Pyrite seen on face at 90° TCA, in slickenslides. Some are straight, while on the same face, slickens in py are curved.		1	1		1	
10		196.23	213.35	GND: Return of frequent quartz, qtz/carb and sulphide veins/veinlets, with wide selvages. Section is ~40% unaltered GND. Slickensides on margins of quartz vein at 90° TCA at 196.23m, in biotite, chlorite and s. From ~203.0m to 203.5m, alteration (chl,cb) appears to be confined between 2 quartz veins. This is where carb veins are concentrated as well. Two Carb veins (0.5cm and 1cm) between 212.24 and 212.35m contain vg in rounded 2-3mm form. This zone - 211.84 - 213.0m - is also a shear zone. Strong slickensides on sulphide covered fracture at 10° TCA in calcite and sericite. Adjacent to this face is an obviously sheared qtz vein with indication of sinistral movement along this 10° face. Slickensides are at 60° TCA.		2	3		2	
10		213.35	231.12	GND: 80% unaltered GND; widest selvage is 80cm and is associated with increased mineralization (pyrite veins). Qtz veins with low mineralization have only small qtz/chl/cb selvages (<3cm); Slickensides with py at 229.45m on fracture face at 20° TCA (similar to at 211 - 213m).						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	9.0	9.0	40						2.0	0.1		2.0					1.0				B364351	189.88	191.07	**2.2**			VA05074726	1.19
4	1	2.0	5.0	40	60	2.0	q/cb	2	0		3.0	0.1										B364352	191.07	192.31	**0.237**			VA05074726	1.24
3	1	1.3	2.7	50	65	1.0	q/cb	2			0.1							3.0				B364353	192.31	193.55	**0.101**			VA05074726	1.24
1	3	0.4	0.4	40		2.0	q/cb	3			4.0	1.0																	
4	1	2.0	4.0	50	90	1.0	q/chl	3	0	15.0	10.0							1.0				B364354	193.55	195.08	**0.312**			VA05074726	1.53
6	1	2.0	7.0	65	50	20.0	cb/chl	5	0	10.0												B364355	195.08	196.23	**0.369**			VA05074726	1.15
																						B364356	BLANK		**<0.006**			VA05074726	
5	1	2.0	5.0	40	90	40.0	cb/chl	4	1	10.0	8.0							3.0				B364357	196.23	197.75	**0.653**			VA05074726	1.52
2	6	0.4	0.7	50	30	10.0	cb/q	4																					
3	1	1.4	3.0	20	45	15.0	q/chl	4	1	0.1	0.1							3.0				B364358	197.75	199.28	**0.168**			VA05074726	1.53
3	4	0.7	1.2	40	55	10.0	q/s	4	1																				
4	1	1.5	3.0	35		18.0	q/cb/chl	5	1		2.0							3.0				B364359	199.28	200.80	**8.88**			VA05074726	1.52
3	6	1.0	3.0	60	40	20.0	cb/chl	5	1	100.0								4.0											
1	4	0.8	0.8	40		10.0	q/cb/s	5	1																				
2	1	1.0	2.0	45		1.0	q	3	0	0.1												B364360	200.80	201.45	**0.162**			VA05074726	0.65
2	3	3.0	3.3	35		9.0	q/chl	5		2.0								5.0											
4	1	1.2	4.0	35	55	6.0	q/chl	4							0.1			4.0				B364361	201.45	202.69	**0.202**			VA05074726	1.24
4	1	1.2	4.0	35	55	6.0	q/chl	4							0.1			4.0				B364362	201.45	202.69	**0.198**	DUP		VA05074726	1.24
4	1	3.0	6.0	50		0.0																B364363	202.69	204.21	**0.29**			VA05074726	1.52
3	3	1.0	3.0	80	45	50.0	q/cb/chl	5	1	0.1								5.0											
4	1	2.5	5.8	35	60	1.0	q	1			0.1							2.0				B364364	204.21	205.74	**0.107**			VA05074726	1.53
2	3	0.9	1.3	55	70	10.0	q/cb/chl	5	0	60.0								2.0											
4	1	2.0	5.0	30	50	20.0	q/cb/chl	5	1		12.0											B364365	205.74	207.27	**0.468**			VA05074726	1.53
5	1	4.5	8.0	35	45	30.0	cb/chl	4		10.0						0.1		1.0				B364366	207.27	208.79	**0.652**		Trace VG	VA05074726	1.52
3	6	0.5	1.3	25		60.0	cb	4		100.0								4.0											
							chl	3																					
2	1	1.5	2.2	60		18.0	cb/chl	3		13.0						0.1		1.0				B364367	208.79	210.32	**0.316**		Trace VG	VA05074726	1.53
3	4	2.0	2.8	30	50	50.0	cb/chl	4																					
4	1	1.0	4.0	40	60					0.1	0.1		0.1			0.1	0.1		5.0			B364368	210.32	211.84	**0.471**		Trace VG, Moly	VA05074726	1.52
1	4	0.5	0.5	60																									
4	1	1.0	4.0	40	60					0.1	0.1		0.1			0.1	0.1		5.0			B364369	210.32	211.84	**0.476**	PD/CA		VA05074726	1.52
1	4	0.5	0.5	60																									
																						B364370	STANDARD 5E		**1.265**	5E		VA05074726	
3	1	1.2	3.2	45		24.0	cb/chl	4	1		3.0											B364371	211.84	212.54	**0.386**			VA05074726	0.70
2	4	1.0	1.5	80		40.0	cb/chl	4								2.0	0.1												
1	1	5.0	5.0	50		38.0	chl/cb	4	1	40.0						2.0		3.0				B364372	212.54	213.35	**0.371**			VA05074726	0.81
4	1	1.0	2.2	40		1.0	q/cb	4	0	2.0	5.0											B364373	213.35	214.88	**0.168**			VA05074726	1.53
5	1	0.5	2.1	40	130	1.0	q/cb	4	0		4.0	1.0										B364374	214.88	216.41	**0.221**			VA05074726	1.53
1	6	0.6	0.6	37		0.0				80.0								5.0											
1	1	0.4	0.4	65	0					0.0												B364375	216.41	217.93	**0.075**			VA05074726	1.52
																						B364376	BLANK		**<0.005**			VA05074726	
3	1	0.5	1.5	45	65	1.0	q	3	0	0.1	2.0											B364377	217.93	219.45	**0.614**			VA05074726	1.52
6	1	0.5	3.0	50		2.0	q	2	0		1.0		1.0						4.0			B364378	219.45	220.98	**0.361**			VA05074726	1.53
5	1	4.0	7.3	60		2.0	q/cb	4	0	4.0								1.0				B364379	220.98	222.51	**2.88**			VA05074726	1.53
2	6	0.5	1.0	60		80.0	cb/chl	4	1	100.0								0.0				B364380	222.51	224.03	**0.468**			VA05074726	1.52
5	1	1.0	4.0	50	60	2.0	q/cb	3			0.1				0.1							B364381	224.03	225.56	**1.32**			VA05074726	1.53
5	1	1.0	4.0	50	60	2.0	q/cb	3			0.1				0.1							B364382	224.03	225.56	**0.665**	DUP		VA05074726	1.53
5	1	1.0	5.0	40	55	2.0	q/chl	2	0		8.0											B364383	225.56	227.08	**1.015**			VA05074726	1.52
1	6	0.3	0.3	50		15.0	cb/chl	4		100.0								4.0											
2	1	1.0	2.0	50		2.0	q/chl	2	0		3.0											B364384	227.08	228.61	**0.39**			VA05074726	1.53
3	3	1.0	3.0	60	50	4.0	q/chl	3			10.0		0.1					3.0											
4	1	1.0	3.0	20	60	1.0	q/cb	4			8.0											B364385	228.61	230.12	**0.309**			VA05074726	1.51
5	1	1.0	4.0	40	60	1.0	q/cb	3			5.0											B364386	230.12	231.12	**0.611**			VA05074726	1.00

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 13 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.12	239.27	GND: Medium grained, with varying degrees of chl, cb, s and q alteration in selvages and along shear planes; These shear planes are at ~0-10° TCA and show an abrupt change from 'clean' GND to carb-infused or chl/cb alt'd GND; Also have slickensides in sericite and clay minerals. This is between 236.5 and 237.9m. Minor slickensides continue to end of section. Interesting note: lower (deeper) selvage around a vein is larger than the upper (shallower) selvage, due to gravity.	1	2	3	1	2	
10		239.27	281.94	GND: Unaltered GND with sheeted quartz veins. Alteration restricted to a few <1m zones, noted below. Slickenslides throughout section on 0-45° fracture faces (rough to smooth). Between 255m and 261m a weak foliation develops in GND, at 120° TCA. Also, rock appears somewhat coarser-grained here, with an increase in 5mm carbonat, 5mm feldspars, 1cm quartz and 3mm black biotite. Length-wise to core, 4cm wide oxidized carb and iron section from 259.2 to 260.6m. At 264.85 - 266.02m, rock is solid selvage around 2 carb veins (3cm and 2cm wide). Their selvages are dominated by chlorite, but are still competent core. Scratchable with a nail. Carb is fine-grained in these selvages; overall color is yellowish deep green. At 267.2 - 267.37m is a dyke of mafic, aphanitic silicified rock. Coarse GND surrounds it on either side, with extra carbonate as well, for ~8cm on either side. Appears like lamprophyre dike. Intersects GND at ~50° TCA. From 276.5 - 276.95m another solid green selvage surrounding 2 quartz veins close together. Again, from 279.05 - 280.2m is a highly chloritized and moderately carbonitized zone. Sulphides disseminated t	1		1		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 14 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	5.5	10.0	60		11.0	chl/q/s	4	1	15.0	5.0		0.1					2.0				B364387	231.12	232.32	**1.65**		Aspy at margins; Py and po in lenses in qtz	VA05074726	1.20
4	1	1.3	4.5	60		1.0	q	3	0		3.0		0.1		0.1				4.0			B364388	232.32	233.17	**0.291**			VA05074726	0.85
4	1	1.3	4.5	60		1.0	q	3	0		3.0		0.1		0.1				4.0			B364389	232.32	233.17	**0.21**	PD/CA		VA05074726	0.85
																						B364390	STANDARD 2B		**NSS**	2B		VA05074726	
6	1	1.1	4.5	40	60	8.0	q/chl	3	0	0.1	4.0		0.1									B364391	233.17	234.69	**0.748**			VA05074726	1.52
1	3	0.5	0.5	55		10.0	q/chl	4		4.0	2.0		0.1						4.0								Aspy in selvage		
5	1	1.0	5.0	60		8.0	q/chl	3			1.0		0.1									B364392	234.69	236.22	**1.01**			VA05074726	1.53
1	1	9.5	9.5	45		20.0	q/cb/chl	4	1	8.0				0.1								B364393	236.22	237.44	**10.2**			VA05074726	1.22
3	1	1.2	3.0	50	30	15.0	q/chl	4	2	5.0	2.0							5.0				B364394	237.44	238.03	**0.969**		Ox'd py in selvage	VA05074726	0.59
3	1	2.0	4.0	45		120.0	q/cb/chl	5	1	0.1								5.0				B364395	238.03	239.27	**0.351**		Selvage for both vein types	VA05074726	1.24
3	3	1.0	2.0	20		120.0	chl/s	5																					
																						B364396	BLANK		**<0.005**			VA05074726	
3	1	1.0	3.0	50	30	2.0	q/chl	3	0		2.0							2.0				B364397	239.27	240.80	**0.393**			VA05074726	1.53
5	1	1.2	4.5	70	45	2.0	q/cb	2		0.1	9.0				3.0				5.0			B364398	240.80	242.32	**0.528**		~5% aspy all alt'd to scorodite	VA05074726	1.52
4	1	2.0	6.0	45	30	2.0	q/cb	2	0		4.0											B364399	242.32	243.85	**0.304**			VA05074726	1.53
5	1	2.0	6.0	30	50	2.0	q/cb	2	0		9.0	0.1	0.1		0.1							B364400	243.85	245.36	**0.627**		Sulphides all found in vein	VA05074726	1.51
2	1	1.2	2.0	50		1.0	q/cb	3	1		2.0	0.1			0.1							B364401	245.36	246.89	**0.994**			VA05074726	1.53
1	3	2.0	2.0	50		3.0	q/cb	4	0		20.0	0.1																	
2	1	1.2	2.0	50		1.0	q/cb	3	1		2.0	0.1			0.1							B364402	245.36	246.89	**0.755**	DUP		VA05074726	1.53
1	3	2.0	2.0	50		3.0	q/cb	4	0		20.0	0.1																	
3	1	1.0	3.0	45		0.5	q	3			3.0	5.0							4.0			B364403	246.89	248.41	**1.1**			VA05074726	1.52
4	1	3.0	4.5	20	35	10.0	q/chl	4	1				0.1					5.0				B364404	248.41	249.94	**0.498**			VA05074726	1.53
5	1	5.0	8.5	40		2.0	q/cb	3		3.0	6.0	2.0	0.1									B364405	249.94	251.46	**3.88**			VA05074726	1.52
4	1	1.0	3.5	40		1.0	q/cb/chl	2	0		5.0											B364406	251.46	252.99	**0.43**			VA05074726	1.53
1	3	0.5	0.5	45		2.0	q/cb	4	0						0.1							B364407	252.99	254.51	**1.375**			VA05074726	1.52
3	1	1.0	2.5	50		0.0					2.0																		
3	1	1.0	2.2	50	40	0.5	q	3	0													B364408	254.51	256.03	**0.804**			VA05074726	1.52
1	3	0.4	0.4	40		1.0	q/cb	3	0		40.0																		
3	1	1.0	2.2	50	40	0.5	q	3	0													B364409	254.51	256.03	**0.8**	PD/CA		VA05074726	1.52
1	3	0.4	0.4	40		1.0	q/cb	3	0		40.0																		
																						B364410	STANDARD 7G		**4.87**	7G		VA05074726	
4	1	1.5	4.5	40		10.0	q/cb/s	5			10.0	1.0	4.0	5.0					2.0	3.0		B364411	256.03	257.56	**1.515**			VA05074726	1.53
2	1	0.5	1.0	50		0.0					6.0	0.1	4.0						1.0	2.0		B364412	257.56	259.09	**0.602**			VA05074726	1.53
4	1	0.1	4.2	45		1.5	q/cb/s	3	1		15.0									2.0		B364413	259.09	260.60	**1.865**			VA05074726	1.51
5	1	1.0	3.2	50	30	2.0	q/cb/s	4	1	3.0	4.0							5.0		2.0		B364414	260.60	262.13	**1.355**			VA05074726	1.53
4	1	0.5	2.0	40	35	2.0	q/cb/s	4	1	1.0	4.0							4.0				B364415	262.13	263.65	**0.601**			VA05074726	1.52
																						B364416	BLANK		**<0.005**			VA05074726	
3	1	0.5	1.5	45		0.4	q/cb	3	0		3.0								2.0			B364417	263.65	264.85	**0.592**			VA05074726	1.20
2	1	1.5	2.0	45		0.0																B364418	264.85	266.02	**0.913**			VA05074726	1.17
2	4	3.0	5.0	30	50	40.0	q/chl/cb	5		15.0								5.0											
3	1	0.5	1.5	45		0.5	q	3			2.0	0.1	2.0		0.1				3.0			B364419	266.02	266.70	**0.464**			VA05074726	0.68
2	1	0.5	1.0	50		1.0	q/cb	3			2.0											B364420	266.70	268.22	**0.102**			VA05074726	1.52
1	6	1.0	1.0	130		25.0			2																				
5	1	2.0	5.2	60	30	4.0	q/cb/s	4	1		3.0											B364421	268.22	269.75	**0.8**			VA05074726	1.53
5	1	2.0	5.2	60	30	4.0	q/cb/s	4	1		3.0											B364422	268.22	269.75	**0.526**	DUP		VA05074726	1.53
2	1	1.0	2.0	60	50	2.0	q/cb	3					0.1						5.0	5.0		B364423	269.75	271.28	**0.367**			VA05074726	1.53
2	1	0.5	1.0	75		1.0	q	5	0										5.0	5.0		B364424	271.28	272.56	**0.448**		Ox'd staining on selvages	VA05074726	1.28
4	6	1.0	1.8	60	100	18.0	chl/q	3	2	95.0								5.0											
2	1	30.0	31.5	45		8.0	chl/q	4		2.0			0.1				0.1					B364425	272.56	273.03	**0.202**		moly	VA05074726	0.47

DRILL LOG LEGEND - P1	DATE: Aug 14 - 20, 2005	PAGE 15 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		281.94	304.05	GND with very little alteration. Selvage size and intensity increase with sulphide content in veins.		1	1		1	
10		304.05	308.02	GND: Section is moderately to highly altered with carb/chl/ser and silicification; Overall color is blue-yellow green; Carb appears partially oxidized (yellow) in veins, veinlets and coarse grains in selvages.	1	2	3		2	
				EOH						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	1.0	2.2	50		2.0	q/cb	2			20.0	0.1	0.1									B364426	273.03	274.32	0.193		Sulph's replaced by mica?	VA05074726	1.29
1	6	3.0	3.0	45		0.0													5.0	5.0									
1	3	1.0	1.0	35		2.0	q/s/cb	4			10.0																		
4	1	1.0	3.0	50		2.0	q/cb	3	0		10.0		0.1									B364427	274.32	275.84	0.608		Aspy in selvage	VA05074726	1.52
3	1	1.2	3.4	40		18.0	q/chl/cb	5		5.0	7.0		0.1									B364428	275.84	277.36	0.045			VA05074726	1.52
3	1	1.2	3.4	40		18.0	q/chl/cb	5		5.0	7.0		0.1									B364429	275.84	277.36	0.044	PD/CA		VA05074726	1.52
																						B364430	STANDARD 4D		0.459	4D		VA05074726	
4	1	1.0	4.0	60	50	2.0	q/cb/chl	3	0		3.0											B364431	277.36	278.89	0.236			VA05074726	1.53
3	1	1.0	2.5	65	45	30.0	chl/q/cb	4	1	4.0	2.0		0.1				0.1					B364432	278.89	280.42	0.434			VA05074726	1.53
3	1	1.0	2.8	50		1.0	cb/q	2		2.0	2.0											B364433	280.42	281.94	0.386			VA05074726	1.52
3	1	0.5	1.5	65		4.0	q/chl	4			3.0											B364434	281.94	283.46	0.678			VA05074726	1.52
5	1	1.0	2.6	45	60	1.0	q/cb/chl	4	0		4.0								5.0	4.0		B364435	283.46	284.99	0.438			VA05074726	1.53
																						B364436	BLANK		<0.005			VA05074726	
6	1	1.0	5.0	40		3.0	q/cb	3			2.0		2.0						4.0			B364437	284.99	286.52	1.215			VA05074726	1.53
1	1	6.0	6.0			25.0	q/chl	5		20.0	25.0																		
							cb/s	3																					
1	1	1.0	1.0	50		0.0				4.0								5.0				B364438	286.52	288.04	0.948			VA05074726	1.52
1	3	1.0	1.0	5	5		5	/cb	3	0.0	1.0	5.0						5.0	1.0										
1	4	1.0	1.0	12		0.0				0.0																			
1	4	0.5	0.5	10		0.0				0.0												B364439	288.04	289.56	0.081			VA05074726	1.52
2	1	1.5	2.5	40	55	3.0	q	2	0		1.0					0.1													
1	3	2.0	2.0	50		8.0	q/chl/cb	3	1	0.1	0.1							5.0	5.0	5.0									
3	1	1.2	3.0	50		4.0	q/s	3														B364440	289.56	291.08	2.01			VA05074726	1.52
2	4	1.0	1.3	20	10						5.0		0.1						5.0										
1	1	1.5	1.5	50		70.0	q/chl/s	5	0		5.0											B364441	291.08	292.60	0.201			VA05074726	1.52
1	1	1.5	1.5	50		70.0	q/chl/s	5	0		5.0											B364442	291.08	292.60	0.326	DUP		VA05074726	1.52
2	1	2.0	3.0	40		40.0	q/s/chl	5		10.0			0.1					5.0				B364443	292.60	294.13	0.359		Sulph vein adj to qtz vn	VA05074726	1.53
1	6	0.5	0.5	40																									
2	1	1.2	2.2	50		4.0	q/chl/cb	4			3.0		0.1									B364444	294.13	295.66	0.447			VA05074726	1.53
4	1	0.6	2.0	50	70	4.0	q	2														B364445	295.66	297.18	0.861			VA05074726	1.52
3	3	1.5	3.7	50		6.0	q/cb	4			30.0																		
2	1	1.0	2.0	60		2.0	q	4			3.0	0.1										B364446	297.18	298.74	0.398			VA05074726	1.56
1	3	0.5	0.5	60		2.0	q/cb	5											5.0										
3	1	1.0	3.0	40	60	2.0	q/chl	3			5.0		1.0									B364447	298.74	300.23	0.169			VA05074726	1.49
5	1	1.0	5.0	60		6.0	q/chl	3	0		5.0											B364448	300.23	301.75	0.564			VA05074726	1.52
1	6	1.0	1.0	50		20.0	s/cb/chl	5	1	100.0								5.0											
5	1	1.0	5.0	60		6.0	q/chl	3	0		5.0											B364449	300.23	301.75	0.595	PD/CA		VA05074726	1.52
1	6	1.0	1.0	50		20.0	s/cb/chl	5	1	100.0								5.0											
																						B364450	STANDARD 5E		1.295	5E		VA05074726	
2	1	2.5	4.0	50		0.0					3.0		0.1									B364451	301.75	303.28	0.521			VA05074726	1.53
2	4	0.4	0.8	15		0.0				0.0																			
5	1	1.5	3.5	60		1.0	q/cb/chl	4		10.0	5.0											B364452	303.28	304.05	0.478			VA05074726	0.77
2	1	2.0	2.5	30	50	30.0	chl/cb	4	1	20.0								2.0				B364453	304.05	305.30	0.215			VA05074726	1.25
1	3	1.0	1.0	55		6.0	q/chl/cb	4	1	20.0								2.0											
1	1	1.0	1.0	20		30.0	chl/cb	4	1	2.0								5.0				B364454	305.30	306.31	0.081			VA05074726	1.01
2	3	0.5	0.8	60	45	20.0	chl/cb/q	4	1		2.0																		
3	1	2.5	3.3	70	50	20.0	cb/chl/q	3		3.0			2.0					5.0				B364455	306.31	307.17	0.496			VA05074726	0.86
																						B364456	BLANK		<0.005			VA05074726	
1	3	1.5	1.5	20		50.0	chl/cb	4		0.1								5.0				B364457	307.17	307.83	1.08			VA05074726	0.66
1	1	0.5	0.5	40		4.0	q/cb/chl	3			10.0		3.0																
1	3	0.8	0.8	25		40.0	chl/cb/q	4		10.0			0.1					3.0											

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-302C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1178m

BEARING: 000 | DIP: -50°

DATES DRILLING: Aug 1 - 5, 2005 | DATES LOGGING: Aug 21 - 28, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 460051 NORTHING: 7099266

COORD SYSTEM: NAD 83: EASTING: 459933 NORTHING: 7099451

NAD 27 (CORRECTED for historic grid): EASTING: 460021 NORTHING: 7099276

SECTION LINE (Historic Grid): 460025 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 0 - 4.57m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B363773 - B363853

Requisition #: MASP448STRGOL.05Q Date Shipped: 26-Aug-05

Lab Record #: VA05074725 Date Received: 2-Sept-05

Sample Sequence: B363854 - B363973

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Aug-05

Lab Record #: VA05074196 Date Received: 2-Sept-05

Sample Sequence: B363974 - B364052

Requisition #: MASP448STRGOL.05Q Date Shipped: 2-Sept-05

Lab Record #: VA05078596 Date Received: 15-Sept-05

Duplicates:	363782; 363802; 363822; 363842; 363862; 363902; 363922; 363942; 363962; 363982; 364002; 363422; 363442
Preparation Duplicate/ Check Assay:	363789; 363809; 363829; 363849; 363869; 363889; 363909; 363929 363949; 363969; 363989; 364009; 364029; 364049
Standards:	363870 (4D); 363810 (2B); 363830 (3C); 363850 (5E); 363870 (4D); 363890 (3C); 363910 (2B); 363930 (5E); 363950 (3C); 363970 (4D); 363990 (1A); 364010 (7G); 364030 (6F); 364050 (6F)
Blanks:	363776; 363796; 363816; 363836; 363856; 363876; 363896; 363916; 363936; 363956; 363976; 363996; 364016; 364036

FROM	TO	LITHOLOGY
0.00	4.57	Casing
4.57	306.92	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
76.20	341.2	-48.9	007.2	008.2
152.39	342.6	-49.2	008.6	009.6
228.59	342.9	-50.1	008.9	009.9
306.92	344.5	-50.2	010.5	011.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 1 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00-4.57	0.00	4.57	Casing						
10	2.57-306.93	4.57	9.14	GND: Broken up, moderately limonitic GND; Oxidation occurs among fracture/vein selvages and fracture faces; Size of core ~5cm long on average; No other alteration apparent; Quartz veins commonly contain limonite stained vugs.	3					
10		9.14	29.26	GND: GND is less broken up than previous (4.57 - 9.14m); Limonite is more pervasive with interval of extremely oxidized GND; Edges of limonite are commonly remnant sericite +/- chlorite alteration overprinted by limonite; Intervals of unaltered grey GND are also common (ex. 20.90 - 21.64m); Quartz veins tend to be vuggy (~5%)	4					
10		29.26	70.32	GND: Grey GND that has undergone intensive oxidation; Oxidation appears to be associated with fractures (commonly cb/calcite filled) and overprints any previous alteration; Previous alteration can still be distinguished (rusty green) eg. 35.88 - 36.18m, oxidation, sericite alteration; Several intervals of unaltered grey GND are present (60cm max) 42.37 - 42.97m; Quartz vein in oxide selvages commonly have limonite stained vugs; From 48.77 - 50.29m core is extremely carbonate altered, crumbly to clayey and limonitic; Quartz veins tend to be small (2-4mm average) with low sulphide content; Low angle (~10° TCA) limonite carbonate lined fractures common throughout - possible fault gouge? (up to 0.5cm); At 69.23m - 8cm limonitic clay interval with polished (no slickenlines) face up hole, having sharp contact with limonite GND and gradual contact downhole at 30° TCA.	3					

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	1	0.5	1.0	45						0.1								2.0				B363773	4.57	6.10	1.430			VA05074725	1.53
0																						B363774	6.10	7.62	0.067			VA05074725	1.52
3	1	0.3	0.8	45														10.0				B363775	7.62	9.14	0.624			VA05074725	1.52
																						B363776	BLANK		0.005			VA05074725	
3	1	0.3	0.7	45														10.0				B363777	9.14	10.67	0.139			VA05074725	1.53
3	1	0.5	1.0	45		0.5	q	3	4									10.0				B363778	10.67	12.19	0.325			VA05074725	1.52
1	3	0.5	0.5	45														20.0											
5	1	0.5	1.5	45	30	0.4	q	4	4									10.0				B363779	12.19	13.72	0.133			VA05074725	1.53
2	1	0.5	0.7	30	45					0.1								2.0				B363780	13.72	15.24	0.125			VA05074725	1.52
5	1	1.2	2.0			0.5	q	5	2		2.0	1.0						3.0				B363781	15.24	16.76	0.084			VA05074725	1.52
5	1	1.2	2.0			0.5	q	5	2		2.0	1.0						3.0				B363782	15.24	16.76	0.046	DUP		VA05074725	1.52
1	1	0.5	0.5	40														5.0				B363783	16.76	18.29	0.055			VA05074725	1.53
1	4	0.2	0.2	40		4.0	cb	3	4									50.0											
4	4	1.0	2.0	45	85	5.0	cb	3	4									75.0				B363784	18.29	19.81	0.092			VA05074725	1.52
3	1	0.5	1.0	45														5.0											
1	5	0.3	0.3	30							2.0											B363785	19.81	20.90	0.072			VA05074725	1.09
5	1	0.6	1.2	45		1.5	q/s	5	1		2.0											B363786	20.90	21.64	0.125			VA05074725	0.74
5	1	0.5	1.5	50														5.0				B363787	21.64	22.86	0.096			VA05074725	1.22
1	4	0.6	0.6	45														90.0											
8	1	0.5	3.0	45		0.3	q	4	2									4.0				B363788	22.86	24.38	0.101			VA05074725	1.52
1	4	0.8	0.8	45														90.0											
8	1	0.5	3.0	45		0.3	q	4	2									4.0				B363789	22.86	24.38	0.078	PD/CA		VA05074725	1.52
1	4	0.8	0.8	45														90.0											
																						B363790	STANDARD 4D		0.453	4D		VA05074725	
3	1	0.5	1.5	45		0.5	q	4	2	0.1								2.0				B363791	24.38	25.91	0.117			VA05074725	1.53
7	1	0.5	2.0	45		0.5	q	4	2		2.0		0.1					2.0				B363792	25.91	27.43	0.163			VA05074725	1.52
7	1	0.5	2.5	30		0.5	q/cb	4	3		2.0							5.0				B363793	27.43	29.26	0.090			VA05074725	1.83
2	3	2.5	2.7	30														50.0											
1	4	0.3	0.3	30														1.0											
2	1	0.5	1.0	30														5.0				B363794	29.26	30.48	0.160			VA05074725	1.22
1	3	0.5	0.5	45		1.5	s/chl	4	2									20.0											
5	1	0.5	2.2	45		1.5	s/chl	4	2									2.0				B363795	30.48	32.00	0.091			VA05074725	1.52
																						B363796	BLANK		<0.005			VA05074725	
4	1	0.5	2.0	45	60						1.0		1.0					5.0				B363797	32.00	33.53	0.136			VA05074725	1.53
2	1	1.0	1.2	45		3.0	s/cb	3	3									5.0				B363798	33.53	35.05	0.056			VA05074725	1.52
6	1	0.5	2.5	45		0.5	s/cb	4	4													B363799	35.05	36.58	0.117			VA05074725	1.53
1	3	1.0	1.0	45														90.0											
7	1	0.8	3.0	45	60	1.0	5	4	4		1.0		1.0					2.0				B363800	36.58	38.10	0.039			VA05074725	1.52
3	1	0.6	1.0	30	45						1.0		1.0					1.0				B363801	38.10	39.62	0.038			VA05074725	1.52
3	1	0.6	1.0	30	45						1.0		1.0					1.0				B363802	38.10	39.62	0.056	DUP		VA05074725	1.52
10	1	0.6	3.0	45	30	1.0	q	4	2		2.0		1.0					2.0				B363803	39.62	41.15	0.117			VA05074725	1.53
6	1	0.8	2.2	45	30						2.0	0.1	1.0					1.0				B363804	41.15	42.67	0.167			VA05074725	1.52
8	1	0.5	2.4	45							2.0		0.1					2.0				B363805	42.67	44.20	0.124			VA05074725	1.53
2	1	0.3	0.5	45		1.0	5	1	1									5.0				B363806	44.20	45.72	0.052			VA05074725	1.52
2	1	0.5	0.7	45		0.3	1	q	5	1.0								1.0				B363807	45.72	47.24	0.316			VA05074725	1.52
8	1	1.0	3.0	45	30													5.0				B363808	47.24	48.77	0.071			VA05074725	1.53
8	1	1.0	3.0	45	30													5.0				B363809	47.24	48.77	0.105	PD/CA		VA05074725	1.53
																						B363810	STANDARD 2B		3.000	2B		VA05074725	

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		70.32	100.58	GND: Grey GND similar to previous interval (29.26 - 70.32m) only limonite is less extensive, except locally at 79.85 - 80.4m where core is extremely limonitic with sharp contact @ 35° TCA; Non oxidized GND is more dominant where quartz veins occur in limonitic selvages, sulphides are oxidized and veins are left vuggy; Fracture faces still limonitic, commonly with carb/calcite; From 77.35 - 77.5m, 50% of core silicified with 5% biotite and 2 % acicular crystals (bismuth?) - slightly oxidized at edges of silicification - no observed sulphides; At 94.0m chl alteration is more intense around pyrrhotite then the rest of the quartz veins; Slickenlines @ 83.82m wi face at 30° and lines at 45°.	2					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B363811	48.77	49.75	0.145			VA05074725	0.98
0																						B363812	49.75	50.93	0.440			VA05074725	1.18
4	1	1.0	2.0	30	70													5.0				B363813	50.93	51.82	0.092			VA05074725	0.89
2	1	0.4	0.6	45														4.0				B363814	51.82	53.34	0.143			VA05074725	1.52
3	1	0.3	0.9	45														5.0				B363815	53.34	54.86	0.257			VA05074725	1.52
																						B363816	BLANK		0.006			VA05074725	
2	1	0.8	1.6	30														2.0				B363817	54.86	56.39	0.100			VA05074725	1.53
2	1	0.6	4.0	45														3.0				B363818	56.39	57.91	0.052			VA05074725	1.52
0																						B363819	57.91	59.44	0.079			VA05074725	1.53
4	1	0.3	0.9	35														4.0				B363820	59.44	60.96	0.038			VA05074725	1.52
2	1	0.4	0.6	40	30	0.6	q	3	1									2.0				B363821	60.96	62.48	0.021			VA05074725	1.52
2	1	0.4	0.6	40	30	0.6	q	3	1									2.0				B363822	60.96	62.48	0.033	DUP		VA05074725	1.52
2	1	0.5	1.0	45														2.0				B363823	62.48	64.01	0.034			VA05074725	1.53
5	1	0.5	2.0	45	30	0.3	q	4	1									2.0				B363824	64.01	65.53	0.175			VA05074725	1.52
1	1	0.8	0.8	35														5.0				B363825	65.53	67.06	0.063			VA05074725	1.53
1	1	0.8	0.8	30		0.5	s/q	4	3									10.0				B363826	67.06	68.58	0.205			VA05074725	1.52
1	3	0.5	0.5	30														50.0											
2	1	1.0	1.2	30														2.0				B363827	68.58	70.10	0.086			VA05074725	1.52
0																						B363828	70.10	70.32	0.039			VA05074725	0.22
0																						B363829	70.10	70.32	0.028	PD/CA		VA05074725	0.22
																						B363830	STANDARD 3C		0.094	3C		VA05074725	
2	1	0.3	0.5	45							0.1							1.0				B363831	70.32	71.63	0.044			VA05074725	1.31
1	3	0.3	0.3	45															2.0										
4	1	1.2	3.0	30		1.0	q/chl	5	0		0.1	0.1	0.1									B363832	71.63	72.14	2.250			VA05074725	0.51
2	1	0.3	0.5	30		0.5	q/chl	2	0		1.0											B363833	72.14	73.15	0.046			VA05074725	1.01
5	1	0.5	1.8	30							1.0											B363834	73.15	74.68	0.172			VA05074725	1.53
3	3	0.5	1.0	30		0.5	q/chl	2	0									2.0											
6	1	1.0	3.0	30							1.0	1.0						5.0				B363835	74.68	76.20	0.234			VA05074725	1.52
																						B363836	BLANK		<0.005			VA05074725	
2	3	1.0	1.5	30		1.5	q/chl	4			1.0											B363837	76.20	77.72	0.342			VA05074725	1.52
1	1	0.2	0.2	30																									
8	1	0.5	2.0	30		0.5	chl	5			1.0											B363838	77.72	79.25	0.207			VA05074725	1.53
3	1	0.3	0.9	45							1.0											B363839	79.25	79.85	0.024			VA05074725	0.60
3	1	1.0	1.6	45														5.0				B363840	79.85	80.40	0.085			VA05074725	0.55
6	1	1.0	3.5	35														5.0				B363841	80.40	82.30	0.109			VA05074725	1.90
6	1	1.0	3.5	35														5.0				B363842	80.40	82.30	0.134	DUP		VA05074725	1.90
1	1	0.3	0.3		30													5.0				B363843	82.30	83.82	0.040			VA05074725	1.52
1	4	0.2	0.2		45	1.0	chl	4	2									50.0											
3	1	0.4	1.0	10	30	1.0	chl	3										2.0				B363844	83.82	85.34	0.493			VA05074725	1.52
1	4	0.5	0.5	30		0.3	q/chl	5			1.0							2.0											
4	1	0.5	1.8	35							1.0							1.0				B363845	85.34	86.87	0.019			VA05074725	1.53
3	1	0.5	0.9	30		0.3	q	5			2.0	0.1	1.0									B363846	86.87	88.39	0.014			VA05074725	1.52
1	1	0.4	0.4	30														2.0				B363847	88.39	89.92	0.027			VA05074725	1.53
2	1	0.3	0.5	45	30	0.3	q	5			2.0		2.0					2.0				B363848	89.92	91.44	0.047			VA05074725	1.52
2	1	0.3	0.5	45	30	0.3	q	5			2.0		2.0					2.0				B363849	89.92	91.44	0.085	PD/CA		VA05074725	1.52
																						B363850	STANDARD 5E		1.435	5E		VA05074725	
4	1	0.2	0.8	40		0.5	q	3														B363851	91.44	92.96	0.054			VA05074725	1.52
1	6	1.0	1.0	30		1.0	chl/q	4					30.0					5.0											
4	1	0.5	1.2	30		1.0	q/chl	4			2.0		1.0					2.0				B363852	92.96	94.49	0.086			VA05074725	1.53
1	5	1.0	1.0	45		1.0	chl/q	4			2.0		2.0																
7	1	1.0	5.0	30		1.0	q/chl	3	2		1.0		1.0					1.0				B363853	94.49	96.01	0.153			VA05074725	1.52
9	1	0.6	3.0	30	40	1.0	chl/q	4			2.0		2.0									B363854	96.01	97.54	0.404			VA05074196	1.53
1	5	0.8	0.8	45		0.5	chl/q	3			2.0		10.0					2.0											
4	1	0.6	1.6	30		0.5	q/chl	3			2.0		2.0					1.0				B363855	97.54	99.06	0.245			VA05074196	1.52

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 5 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		100.58	116.52	GND: Grey GND where majority of core has been oxidized with unaltered to non oxidized core in intervals (similar to interval 29.26 - 70.32m); Limonite occurs on all fracture faces commonly with carbonate/calcite; Quartz veins with limonite selvages commonly contain oxidized vugs; Oxidation is moderate except locally as selvage for intensely oxidized, carbonitized and argillic altered interval at 105.47 (5cm) with grey quartz eyes (fault gg?); @ 101.61m ~1cm quartz vein at 30° TCA contains a massive, soft (2-3) black mineral (oxidation product?); Aspy found within black mineral, po and cpy also found in quartz vein; @ 108.44 - 108.77m there is abundant quartz veining or quartz blebs (avg 8x4cm) with 1-2% aspy and trace cpy, proximal to a 2cm quartz vein with 2% aspy.	3					
10		116.52	138.68	GND: Grey GND same as described in interval 70.32 - 100.58m; From 192.4 - 192.75m GND is slightly more mafic with no veining; @ 129.64m a 6cm interval of limonite, carb-rich clay altered GND with remnant quartz eyes; Sharp contact with competent GND at 30°; At 132.69m a 5cm cb-rich, slightly limonitic clay seam with rare <2mmx7mmx2mm quartz eyes, sharp irregular contact at 90°.	2					
10		138.68	141.30	GND is moderately limonitic throughout with locally more intensive selvages with slickenlines (141.08m with face at 40° and lines at 45°); Similar to interval 29.26 - 70.32m; Slickenlines 139.08 with face at 30° and lines at 45°.	3					
10		141.30	142.01	GND intensely oxidized to a rusty yellowish color; Core is soft and becomes softer down hole as argillic alteration intensifies; Core effervesces strongly where it has been altered to clay; Pale lim color possibly due to overprinting of previous alteration (ser?); Quartz veins tend to be irregular and discontinuous; Sharp contact at 142.01m at 45°.	4			4	3	
10		142.01	147.00	GND has undergone intense alteration; Core has a dark green color (chlorite + sericite alteration) but closely examined pale-green-grey (ser alteration); Core interchanges btwn extremely clay altered to slightly clay altered at shallow angles (1-30°); Speckled throughout is euhedral-subhedral, rusty-orange-brown (oxidized) siderite (1-10%); Siderite up to 4x4mm; Siderite dominates core (50%) locally from 142.01 - 142.26m and 146.25 - 146.77m; Quartz veins are broken up and commonly displaced or irregular - appear as breccias (angular quartz clasts randomly oriented).	3	5	5	5	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B363856	BLANK		<0.005			VA05074196	
6	1	1.0	2.0	30		0.3	q/chl	3	2		1.0							4.0				B363857	99.06	100.58	0.367			VA05074196	1.52
5	1	1.0	3.0	30	40	1.0	q/chl	3	2		2.0	0.1	2.0									B363858	100.58	102.11	0.148			VA05074196	1.53
4	1	0.6	1.5	35		1.0	q/s	4	2									10.0				B363859	102.11	103.63	0.197			VA05074196	1.52
4	1	0.5	1.0	30		0.3	q/chl	3	2									2.0				B363860	103.63	105.16	0.078			VA05074196	1.53
6	1	2.0	3.5	40	30								1.0					5.0				B363861	105.16	106.69	0.423			VA05074196	1.53
6	1	2.0	3.5	40	30								1.0					5.0				B363862	105.16	106.68	0.151	DUP		VA05074196	1.52
5	1	0.5	1.6	30		0.2	chl	3	2		1.0		1.0					2.0				B363863	106.68	108.20	0.146			VA05074196	1.52
3	1	2.0	2.5	40									2.0					1.0				B363864	108.20	109.73	2.130			VA05074196	1.53
3	1	2.0	2.7	10	30	0.5	q	4					3.0				0.1					B363865	109.73	111.25	0.272		Mo only in one vein	VA05074196	1.52
2	1	0.2	0.4	30		1.0	q	4	3									5.0				B363866	111.25	112.78	0.088			VA05074196	1.53
3	1	0.6	1.5	20	30	0.2	q	5			2.0		1.0									B363867	112.78	114.30	0.352			VA05074196	1.52
2	1	0.5	1.0	30							2.0							2.0				B363868	114.30	115.82	0.024			VA05074196	1.52
2	1	0.5	1.0	30							2.0							2.0				B363869	114.30	115.82	0.027	PD/CA		VA05074196	1.52
																						B363870	STANDARD 4D		0.481	4D		VA05074196	
3	1	0.6	1.2	40		0.3	q	4	2		2.0							2.0				B363871	115.82	116.52	0.094			VA05074196	0.70
1	1	0.2	0.2	40																		B363872	116.52	117.35	0.196			VA05074196	0.83
6	1	0.6	2.2	40		1.0	chl	3										1.0				B363873	117.35	118.87	0.085			VA05074196	1.52
2	1	0.3	0.5	40		0.5	chl	3			2.0		1.0					1.0				B363874	118.87	120.40	1.730			VA05074196	1.53
1	3	0.3	0.3	40		1.0	5	2	2		2.0							10.0											
4	1	0.2	0.8	40		1.0	chl	2			2.0		5.0									B363875	120.40	121.92	0.233			VA05074196	1.52
																						B363876	BLANK		<0.005			VA05074196	
4	1	0.5	1.4	45							2.0	0.1	2.0									B363877	121.92	123.44	0.125			VA05074196	1.52
3	1	0.6	1.2	40	30						2.0	1.0	4.0									B363878	123.44	124.97	0.284			VA05074196	1.53
2	1	1.0	1.2	45							2.0		1.0									B363879	124.97	126.49	0.125			VA05074196	1.52
1	6	1.2	1.2	30		2.0	s/chl	4			2.0		50.0									B363880	126.49	128.02	0.278			VA05074196	1.53
3	1	0.3	0.7	30		0.5	chl	3			4.0		1.0																
2	3	0.4	0.6	30		0.5	q	5			2.0	0.1										B363881	128.02	129.54	0.043			VA05074196	1.52
1	1	0.2	0.2	45							2.0																		
2	3	0.4	0.6	30		0.5	q	5			2.0	0.1										B363882	128.02	129.54	0.140	DUP		VA05074196	1.52
1	1	0.2	0.2	45							2.0																		
0																						B363883	129.54	131.06	0.082			VA05074196	1.52
3	1	0.5	1.2	40	30	1.0	chl	4			2.0		5.0					2.0				B363884	131.06	132.59	1.725			VA05074196	1.53
2	1	0.5	1.0	40	30	0.3	q	4			1.0		1.0									B363885	132.59	134.11	0.069			VA05074196	1.52
4	1	0.5	1.5	40							2.0		1.0					2.0				B363886	134.11	135.64	0.434			VA05074196	1.53
6	1	0.8	2.5	40							1.0		1.0									B363887	135.64	137.16	0.111			VA05074196	1.52
5	1	0.5	2.2	40		1.0	q	5	2		1.0		1.0					2.0				B363888	137.16	138.68	0.349			VA05074196	1.52
5	1	0.5	2.2	40		1.0	q	5	2		1.0		1.0					2.0				B363889	137.16	138.68	0.386	PD/CA		VA05074196	1.52
																						B363890	STANDARD 3C		0.098	3C		VA05074196	
2	1	1.0	1.5	30														2.0				B363891	138.68	140.21	1.040			VA05074196	1.53
0																						B363892	140.21	141.30	0.285			VA05074196	1.09
1	1	1.0	1.0	30														2.0				B363893	141.30	142.01	0.123			VA05074196	0.71
3	1	2.0	3.0	45														5.0				B363894	142.01	143.57	14.650			VA05074196	1.56
4	1	3.0	8.0	30	45													5.0				B363895	143.57	144.90	5.950			VA05074196	1.33

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 7 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		147.00	153.87	GND moderately limonitic throughout as in interval 138.68 - 141.3m; Slickenlines: @ 150.4m face 20°/lines 25°; @ 151.1m face 30°/lines 60°; @ 149 m face 45°/lines 45° TCA; From 150.3 - 151.1m quartz veins are irregular +/- displaced. Limonite alteration is slightly more intense and locally appears blotchy.	3					
10		153.87	155.00	GND: 2 large white quartz veins that have been moderately fractured (carb filled frac's) with limonite faces; Very low sulphide content (tr aspy + py); Fracturing occurs at low angles (20-30°); Between veins is 5cm of sericite + oxidized GND with slickenlines at 154.18 m face 80°/lines 80° TCA: Contact at 155.0m is sharp at 25° with grey clay containing very fine grained disseminated pyrite and quartz eyes (2x2x2mm average).						
10		155.00	161.54	GND with extensive sericite alteration; Limonite staining along fractures is common; Speckled siderite (up to 4x4mm) and massive along fractures at 157.46m and 155.59m; @ 159.94m, 2 parallel quartz-sulphide veins, 0.5cm py vein and 2cm aspy vein. Pyrite vein is very fine to medium grained. Aspy vein is massive aspy; lim fractures occur in both veins but cross-cut fractures within GND; Slickenlines: @155.4m face at 60° with lines at 85°; @ 156.95m face at 30° with lines at 90°.						
10		161.54	170.69	GND: Grey GND with abundant quartz veining; Larger quartz veins tend to have selvages overprinted by oxidation (previous sericite alteration?); Limonite also occurs from fracturing; Possible fault gouge @ 167.25m at 20° (3cm gg adjacent to 1cm quartz vein); Limonite selvages are soft and slightly carbonate altered. Slickensides: @163.70m face at 30° with lines at 40°; @ 166.12m face at 75° with lines at 75°; @ 166.17m face at 30° with lines at 30°; @ 169.00m face at 40° with lines at 65° TCA.	3					
10		170.69	178.31	GND: Grey GND; Limonite+/- carbonate/calcite still appears on fracture faces; Locally core is limonite throughout from 172.51 - 172.81m where core is highly fractured; Limonite is becoming much less prominent; Slickensides: @172.41m face at 20° with lines at 45°; @ 173.0m face at 10° with lines at 10°; @ 176.68m face at 30° with lines at 90°; @ 176.66m face at 60° with lines at 90° TCA.	3					
10		178.31	180.22	GND: Sericite altered GND that has been oxidized; Locally core is very highly fractured and crumbly.	4	5		3		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 8 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B363896	BLANK		0.005			VA05074196	
1	1	2.5	2.5	45									2.0					5.0				B363897	144.90	146.16	0.123			VA05074196	1.26
5	1	1.5	5.0	30														4.0				B363898	146.16	147.00	0.933			VA05074196	0.84
2	1	2.0	3.0	45	50													2.0				B363899	147.00	148.70	1.120			VA05074196	1.70
6	1	2.0	5.0	30	60								0.1					2.0				B363900	148.70	150.30	0.653			VA05074196	1.60
1	1	0.4	0.4	60														1.0				B363901	150.30	151.10	0.770			VA05074196	0.80
1	1	0.4	0.4	60														1.0				B363902	150.30	151.10	0.301	DUP		VA05074196	0.80
5	1	1.0	3.2	45	30						0.1							1.0				B363903	151.10	152.40	0.447			VA05074196	1.30
2	1	0.5	1.0	30														2.0				B363904	152.40	153.87	0.481			VA05074196	1.47
1	3	0.5	0.5	30														1.0											
2	1	0.3	0.6	45									1.0									B363905	153.87	155.00	2.520			VA05074196	1.13
2	1	0.8	1.3	45									0.1					1.0				B363906	155.00	155.73	0.796			VA05074196	0.73
2	1	2.0	3.0	45									1.0					2.0				B363907	155.73	156.97	1.195			VA05074196	1.24
3	1	2.0	3.0	45									0.1					2.0				B363908	156.97	158.50	0.976			VA05074196	1.53
3	1	2.0	3.0	45									0.1					2.0				B363909	156.97	158.50	0.892	PD/CA		VA05074196	1.53
																						B363910	STANDARD 2B		3.240	2B		VA05074196	
4	1	1.6	45.0	30														2.0				B363911	158.50	159.94	0.299			VA05074196	1.44
2	6	2.5	4.5	30						30.0			30.0					5.0				B363912	159.94	160.02	13.450			VA05074196	0.08
4	1	1.2	2.4	30	40					5.0			4.0					4.0				B363913	160.02	161.54	0.527			VA05074196	1.52
2	3	0.5	0.7	35						5.0			6.0					5.0											
1	6	0.2	0.2	35						90.0								2.0											
7	1	2.0	7.0	30	70								0.1					0.1				B363914	161.54	162.84	0.280			VA05074196	1.30
7	1	6.0	16.0	30	45	7.0	s/cb	3	3				0.1					1.0				B363915	162.84	164.59	3.310			VA05074196	1.75
																						B363916	BLANK		<0.005			VA05074196	
3	1	2.0	6.0	30		3.0	5	4	3				1.0					1.0				B363917	164.59	166.12	0.380			VA05074196	1.53
1	5	0.4	0.4	30		1.0	q	5	2									1.0											
5	1	0.5	2.2	20	40	3.0	5	5	3				1.0					2.0				B363918	166.12	167.64	1.730			VA05074196	1.52
6	1	1.0	4.0	30	40	1.0	5	4			1.0		1.0					2.0				B363919	167.64	169.16	0.442			VA05074196	1.52
5	1	1.1	4.0	30		3.0	s/chl	4	2		1.0		2.0									B363920	169.16	170.69	2.300			VA05074196	1.53
1	3	0.6	0.6	40		2.0	s/chl	4		0.1																			
1	1	10.0	10.0	20		3.0	s/cb	4	3				2.0					1.0				B363921	170.69	171.28	15.550			VA05074196	0.59
1	1	10.0	10.0	20		3.0	s/cb	4	3				2.0					1.0				B363922	170.69	171.28	19.100	DUP		VA05074196	0.59
5	1	1.0	3.4	30	45	1.0	chl	4		2.0			1.0									B363923	171.28	172.21	0.146			VA05074196	0.93
3	1	1.5	2.5	40		1.5	5	5		0.1			2.0									**B363943**	172.21	173.74	0.282		**Missed sample**	VA05074196	1.53
1	5	0.4	0.4	40									1.0																
6	1	1.4	3.0	40		2.0	5	5		0.1	1.0		2.0									B363924	173.74	175.26	0.375			VA05074196	1.52
2	3	0.5	0.9	40		4.0	5	5																					
5	1	1.0	2.2	30		4.0	5	5														B363925	175.26	176.78	1.775			VA05074196	1.52
7	1	2.0	5.0	30		4.0	5	5	2				5.0									B363926	176.78	178.31	3.050			VA05074196	1.53
1	6	1.0	1.0	30		4.0	5	5	2	0.1			40.0																
0																						B363927	178.31	179.83	0.220			VA05074196	1.52
0																						B363928	179.83	180.22	1.135			VA05074196	0.39
0																						B363929	179.83	180.22	1.280	PD/CA		VA05074196	0.39
																						B363930	STANDARD 5E		0.960	5E		VA05074196	

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 9 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.22	181.89	GND: Grey GND with sericite and chlorite alteration; Core is competent; Quartz veins are minimal; Slickenlines: @180.8m face 50°, lines 70°.		4	3			
10		181.89	184.40	GND: Intensely clay and sericite alt'd GND; <2mm py/cb veinlets are common throughout; Fine grained disseminated pyrite occurs locally where core is most intensely altered; Sulphide veins (py) contain dark grey clay (oxidized sulphides?); Core appears brecciated (183.9 - 184.4m) quartz veins are broken up and displaced and crumbly with abundant disseminated pyrite in dark grey clay matrix; Blocks of brecciated (?) core have slickenlines with pyrite smearing.		5		4		
10		184.40	189.22	GND: Highly broken-up and fractured grey GND (longest piece is 12cm); Some blocks appear sericitized; Slickenlines: @187.45m Face at 30° with lines at 70° TCA.						
10		189.22	192.02	GND: Intensely clay and sericite altered GND; Similar to previously described from interval 181.89-184.4m		5		5		
10		192.02	202.91	GND: GND has undergone various degrees of sericite alteration due to fracturing as altered GND tends to have sharp contacts with grey clay and disseminated pyrite or sheared pyrite on slip face; Alteration may be gradual at one end, and sharp at the other end of alteration selvage; K-spar/quartz veins are present, and within sericite selvages are k-spar, and euhedral pyrite xtls; K-spar veins contain some carbonate; No limonite; Slickenlines: @193.80m face at 20°, lines at 60°; @ 196.65m face at 10°, lines at 30°; @ 197.9m face at 45°, lines at 85°; @ 199.1m face at 60°, lines at 85°; @ 199.12m face at 30°, lines at 60°; @ 201.67m face at 5°, lines at 25°.		4				
10		202.91	205.74	GND: Pale green GND; K-Spar alteration appears as selvages, veinlets, and euhedral crystals disseminated throughout; Quartz veins tend to be at very shallow angles; Non K-spar altered core (sericite alteration) is softer than K-altered core; Slickenlines: @205.00m face is at 5° with lines at 50° TCA; Possible sericite overprinting giving K-spar alteration greenish hue?; Quartz veins are commonly irregular +/- displaced.		5				5
10		205.74	210.73	GND: Broken core; @ 205.74 - 207.26m = GND has undergone sericite alteration (4cm selvage avg); @ 207.26 - 210.73m = GND has undergone clay alteration, blocks are smaller and consist of quartz veins and quartz selvages; @ 210.41 - 210.73m = Clay is carb-rich (strong HCL reaction).				4		
10		210.73	216.41	GND: The majority of the GND is sericite altered with scattered euhedral K-spar and veinlets of K-spar throughout; Intervals where GND is not altered (up to 30cm) it is finer grained and darker than normal grey GND.		5				3

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																										
						Selvages				Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.5	0.8	40						2.0			2.0									B363931	180.22	181.89	0.271			VA05074196	1.67
2	3	1.0	1.5	20	40					2.0			2.0																
0																						B363932	181.89	182.36	0.272			VA05074196	0.47
4	1	1.0	3.0	5	45					10.0			5.0									B363933	182.36	182.88	5.130			VA05074196	0.52
1	6	0.3	0.3	5						40.0																			
0																						B363934	182.88	184.40	3.500			VA05074196	1.52
6	1	2.0	4.0	60	45					5.0			3.0									B363935	184.40	185.93	3.350			VA05074196	1.53
2	6	0.4	0.8	60	45					50.0								1.0											
																						B363936	BLANK		0.010			VA05074196	
2	1	2.0	3.0	45		1.0	s	5					0.1									B363937	185.93	187.45	1.165			VA05074196	1.52
1	3	0.5	0.5	45		1.0	5	4																					
2	1	1.0	1.8	60									4.0									B363938	187.45	189.22	0.893			VA05074196	1.77
1	3	0.4	0.4	60		1.0	s	5					1.0																
0																						B363939	189.22	190.50	0.437			VA05074196	1.28
0																						B363940	190.50	192.02	0.715			VA05074196	1.52
3	1	2.5	5.0	30	45					2.0			2.0									B363941	192.02	193.55	1.150			VA05074196	1.53
3	1	2.5	5.0	30	45					2.0			2.0									B363942	192.02	193.55	0.943	DUP		VA05074196	1.53
																						B363943	SEE ABOVE				Missed sample, see above (171.26-172.21m)		
4	1	1.0	3.0	55						1.0	1.0											B363944	193.55	195.07	0.220			VA05074196	1.52
1	2	0.5	0.5	45						1.0																			
3	2	0.5	1.2	55		2.0	s/k	5		2.0			1.0									B363945	195.07	196.46	0.141			VA05074196	1.39
1	1	0.2	0.2	45							0.1																		
0																						B363946	196.46	196.82	0.217			VA05074196	0.36
6	1	0.5	1.8	60	45	3.0	k/s	5		2.0												B363947	196.82	198.31	0.902			VA05074196	1.49
2	1	0.5	0.8	50		1.0	s/k	4			1.0											B363948	198.31	199.64	0.382			VA05074196	1.33
2	1	0.5	0.8	50		1.0	s/k	4			1.0											B363949	198.31	199.64	0.352	PD/CA		VA05074196	1.33
																						B363950	STANDARD 3C		0.095	3C		VA05074196	
8	1	1.0	3.5	50		2.0	5	3			2.0		1.0									B363951	199.64	201.17	0.327			VA05074196	1.53
2	1	0.4	0.6	30	45																	B363952	201.17	202.88	0.466			VA05074196	1.71
2	2	0.8	1.4	45		1.0	k/s	5																					
4	1	2.0	3.0	30	45																	B363953	202.88	204.22	0.763			VA05074196	1.34
1	2	0.4	0.4	30																									
7	1	1.0	2.5	20	10	4.0	k/s	5		0.1												B363954	204.22	205.74	1.795			VA05074196	1.52
2	1	0.3	0.6	45																		B363955	205.74	207.26	0.419			VA05074196	1.52
																						B363956	BLANK		<0.005			VA05074196	
2	1	0.4	0.7	45							2.0											B363957	207.26	209.79	0.709			VA05074196	2.53
0																						B363958	209.79	209.70	0.149			VA05074196	-0.09
0																						B363959	209.70	210.73	0.334			VA05074196	1.03
3	1	8.0	10.0	60		34.0	k/s	5		0.1			2.0									B363960	210.73	211.40	2.320			VA05074196	0.67
2	2	1.0	1.5	45																									
2	1	0.5	1.0	45																		B363961	211.40	213.10	0.084			VA05074196	1.70
1	2	1.5	1.5	55		7.0	s	5																					

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 11 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		216.41	220.45	GND: GND is highly broken up and sericite altered; GND is broken into 4x6x4 cm pieces with argillic alteration; Locally, pieces appear darker green due to chlorite alteration; Quartz veining is minimal; K-spar veinlets are present; Cavings present at 219.62m.		5	3			
10		220.45	222.50	GND: Darker, finer grained GND; Sericite selvages occur along k-spar +/- quartz +/- cb or fractures; Fractures typically have dark-grey-green (chloritic) clay faces; @ 222.09m is a 0.5cm quartz-k spar vein where k-spar is more pink than typical k-spar; Slickenlines: @222.25m with face at 45° and lines at 45°.		5				2
10		222.50	235.24	GND: Similar to previous interval (220.45 - 222.5m) but GND is typical with only local darker, finer grained GND (up to 25cm); Slickenlines: @ 224.03m with face at 65° and lines at 65°.		5				2
10		235.24	242.62	GND: Quartz-rich Granitoid (silicified); Fine grained and very hard; Carbonate fractures are abundant with sericite alteration selvages; Quartz veins are white with clean and sharp contacts with selvages; Slickenlines: @237.84m face at 25° with lines at 40°; @ 239.15m face at 70° with lines at 80°; @ 241.75m with face at 70° with lines at 75° TCA. Silicification (4).						4
10		242.62	259.08	GND: Back into Grey GND with intervals of sericite alteration commonly speckled with k-spar crystals (subhedral); K-spar veins and veinlets common within sericite alteration; Contact with quartz-rich GND is sharp at 50° TCA; @ 247.9m a 10cm zone of intense alteration appears brecciated (dark and light clay veinlets with minor disseminated pyrite); Slickenlines: @ 243.0 face at 10° with lines at 30° TCA; @ 254.31m face at 30° with lines at 85°; @ 254.1m a 1cm quartz vein is displaced twice by 2 dextral slips, the slip plane is on 0.8cm k-spar vein (possibly with carbonate), the slip planes are at 40° and 15°; Slickenlines: @ 255.95m face at 10°, lines at 40°. From 257.90 to 259.08m core is highly clay altered (crumbly) and quartz veins are crumbling.		5				2

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL															Interval						
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	1	0.5	1.0	45																		B363962	211.40	213.10	**0.091**	DUP		VA05074196	1.70
1	2	1.5	1.5	55		7.0	s	5																					
1	1	0.5	0.5	70						5.0												B363963	213.10	213.84	**0.286**			VA05074196	0.74
1	2	1.5	1.5	30																									
0																						B363964	213.84	214.88	**0.308**			VA05074196	1.04
0																						B363965	214.88	216.41	**0.033**			VA05074196	1.53
0																						B363966	216.41	217.93	**0.124**			VA05074196	1.52
1	1	1.0	1.0	20						2.0												B363967	217.93	219.46	**0.398**			VA05074196	1.53
2	1	1.2	1.7	20	5					1.0												B363968	219.46	220.45	**0.485**			VA05074196	0.99
2	1	1.2	1.7	20	5					1.0												B363969	219.46	220.45	**0.481**	PD/CA		VA05074196	0.99
																						B363970	STANDARD 4D		**0.475**	4D		VA05074196	
3	2	1.5	2.2	45	30	14.0	s/k	5		5.0												B363971	220.45	221.70	**0.115**			VA05074196	1.25
2	1	0.5	1.0	45						2.0												B363972	221.70	222.50	**0.092**			VA05074196	0.80
1	1	2.0	2.0	70																									
1	2	0.5	0.5	80						0.1												B363973	222.50	224.03	**0.030**			VA05074196	1.53
2	1	0.3	0.5	30							1.0																		
1	3	0.3	0.3	30						2.0																			
4	2	2.0	2.6	30		3.0	s	5		1.0												B363974	224.03	225.55	**0.170**			VA05078596	1.52
3	1	2.0	3.0	30		2.0	s	5					1.0									B363975	225.55	227.08	**0.373**			VA05078596	1.53
																						B363976	BLANK		**<0.005**			VA05078596	
0																						B363977	227.08	228.60	**0.143**			VA05078596	1.52
1	6	0.4	0.4	60						80.0												B363978	228.60	230.12	**0.059**			VA05078596	1.52
3	1	2.0	3.0	45						1.0												B363979	230.12	231.65	**0.043**			VA05078596	1.53
1	4	0.5	0.5	45																									
2	1	0.5	0.5	45	70					1.0												B363980	231.65	233.17	**0.050**			VA05078596	1.52
2	1	2.0	3.5	30		2.0	s	5		1.0												B363981	233.17	234.15	**0.078**			VA05078596	0.98
2	1	2.0	3.5	30		2.0	s	5		1.0												B363982	233.17	234.15	**0.226**	DUP		VA05078596	0.98
3	1	2.0	3.2	30	45	2.0	s	5		0.1												B363983	234.15	235.24	**0.178**			VA05078596	1.09
1	1	0.5	0.5	30							1.0											B363984	235.24	236.22	**0.037**			VA05078596	0.98
5	1	0.5	0.5	70		2.0	s	5		2.0	1.0											B363985	236.22	237.74	**0.108**			VA05078596	1.52
5	1	2.0	4.0	70		1.5	s	5		12.0	1.0											B363986	237.74	239.27	**0.182**			VA05078596	1.53
3	1	2.0	3.0	70		1.5	s	5		0.1			0.1									B363987	239.27	240.79	**0.186**			VA05078596	1.52
7	1	2.0	6.0	70	60	2.0	s	5			0.1											B363988	240.79	242.62	**0.178**			VA05078596	1.83
5	2	3.0	7.0	70		2.0	s	5			0.1																		
7	1	2.0	6.0	70	60	2.0	s	5			0.1											B363989	240.79	242.62	**0.218**	PD/CA		VA05078596	1.83
5	2	3.0	7.0	70		2.0	s	5			0.1																		
																						B363990	STANDARD 1A		**0.792**	1A		VA05078596	
5	1	2.0	4.5	60	50						0.1		0.1									B363991	242.62	243.81	**0.152**			VA05078596	1.19
1	2	1.0	1.0	50																									
3	2	0.6	1.1	10	60					1.0												B363992	243.81	245.36	**0.462**			VA05078596	1.55
4	1	1.0	3.0	60																									
4	1	1.0	3.0	50	60					0.1												B363993	245.36	246.89	**0.164**			VA05078596	1.53
2	2	1.0	1.5	40	60	5.0	s/k	5																					
3	1	1.0	2.0	45	60						1.0											B363994	246.89	248.41	**0.081**			VA05078596	1.52
2	2	1.0	1.2	45	60	8.0	s/k	5		1.0																			
4	1	2.0	4.0	60		2.0	s/k	5														B363995	248.41	249.94	**0.180**			VA05078596	1.53

DRILL HOLE # : DG05-302C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		259.08	266.90	GND: Back into q-rich granodiorite (silicified) as previously described; Core has less sericite alteration; Contact with grey GND is crumbled; Abundant carbonate fractures/veinlets; K-spar is no longer visible; core is moderately broken up (8cm avg) by steep (60-90°) fractures; Quartz veins are white and clean and commonly fractured adjacent to edges; Quartz veins appear to be post alteration; @ 260.7m coarse grained aspy vein (0.8cm) has crumbled away from 80° face; @ 265.28-265.89m core appears brecciated (quartz vein is broken up and crumbly with fine grained euhedral disseminated veinlets).		5				
10		266.90	272.80	GND: GND is intensely sericite and argillic altered; Core is a pale green colour and very soft; Possibly k-spar alteration was overprinted by sericite alteration as core is beige-green adjacent to veins but still soft; Quartz veins are commonly broken up and crumbly; No observed carbonate/calcite in quartz vein fractures or in GND; @ 268.22m, 16cm quartz vein with grey veinlets throughout contains up to 2.5x2.5x2mm euhedral disseminated pyrite (broken up at either end, no orientation); Slickenlines: @ 267.2m face at 40° with lines at 45° TCA.		5		5		
10		272.80	275.84	GND: GND has been completely sericite altered; Core is harder, darker and more competent than previous interval; Fractures and fracture faces filled with carbonate (less reactive than previously observed).		5		1		
10		275.84	281.12	GND; GND is completely sericite altered with moderate to intense clay alteration; Slickenlines: @ 279.68m face at 30° with lines at 90°.		5		3		
10		281.12	282.23	GND: GND with sericite alteration due to fracturing (carbonate filled fractures)		4				
10		282.23	283.46	GND: Unaltered (slightly more mafic) GND; Fine grained.						
10		283.46	285.51	GND: Unaltered grey GND; Moderate fracturing.						
10		285.51	288.04	GND: Grey GND that has undergone moderate clay alteration; Locally, intensely altered to clay with quartz eyes; Grey-dark grey (2-4mm) clay veins are common at 45° TCA; Slickenlines: @ 287.5m face at 10° with lines at 80°.				4		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 14 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	2	1.5	1.5	50		2.0	s/k	5														B363996	BLANK		<0.005			VA05078596	
5	1	1.5	35.0	40		1.0	s	2			4.0											B363997	249.94	251.46	0.170			VA05078596	1.52
2	2	0.8	1.4	60		1.0	s/k	5																					
4	1	1.0	2.2	60							1.0											B363998	251.46	252.98	0.280			VA05078596	1.52
3	2	3.0	4.5	40	45	5.0	s/k	5																					
4	1	1.0	3.0	40							1.0											B363999	252.98	254.51	0.174			VA05078596	1.53
3	2	0.6	1.6	40	15					1.0																			
3	1	0.5	1.4	60						1.0												B364000	254.51	256.03	1.720			VA05078596	1.52
3	2	0.8	1.4	30	60	3.0	s/k	5																					
1	1	1.0	1.0	60																		B364001	256.03	257.56	0.065			VA05078596	1.53
1	2	0.4	0.4	45		1.0	s	4					0.1																
1	1	1.0	1.0	60																		B364002	256.03	257.56	0.114	DUP		VA05078596	1.53
1	2	0.4	0.4	45		1.0	s	4					0.1																
3	1	2.0	4.0	60	30																	B364003	257.56	259.08	0.156			VA05078596	1.52
9	1	4.0	15.0	85	60																	B364004	259.08	260.60	0.959			VA05078596	1.52
7	1	2.0	5.0	80						0.1												B364005	260.60	262.13	0.182			VA05078596	1.53
1	6	0.8	0.8	80																									
2	1	1.0	1.5	70						1.0												B364006	262.13	263.25	0.206			VA05078596	1.12
6	1	1.0	4.0	70						1.0												B364007	263.25	265.28	0.164			VA05078596	2.03
3	1	4.0	8.0	45						10.0												B364008	265.28	265.89	0.344			VA05078596	0.61
3	1	4.0	8.0	45						10.0												B364009	265.28	265.89	0.365	PD/CA		VA05078596	0.61
																						B364010	STANDARD 7G		4.460	7G		VA05078596	
6	1	0.5	2.5	65						0.1												B364011	265.89	266.90	0.269			VA05078596	1.01
18	2	4.0	18.5	40						10.0			0.1									B364012	266.90	268.22	5.760			VA05078596	1.32
1	6	1.0	1.0	40						10.0			20.0								70.0								
1	1	16.0	16.0							10.0												B364013	268.22	268.38	6.110			VA05078596	0.16
1	1	4.5	4.5	60						0.1			0.1									B364014	268.38	269.75	0.685			VA05078596	1.37
2	1	1.0	2.0	30																		B364015	269.75	271.27	0.722			VA05078596	1.52
																						B364016	BLANK		<0.005			VA05078596	
2	1	0.2	0.4	30																		B364017	271.27	272.80	0.470			VA05078596	1.53
4	1	1.5	4.0	60						0.1												B364018	272.80	274.32	0.229			VA05078596	1.52
3	1	1.0	2.5	45																		B364019	274.32	275.84	0.904			VA05078596	1.52
1	1	0.5	0.5	10																		B364020	275.84	277.00	0.051			VA05078596	1.16
1	1	2.0	2.0	30						0.1												B364021	277.00	278.50	0.558			VA05078596	1.50
1	1	2.0	2.0	30						0.1												B364022	277.00	278.50	0.900	DUP		VA05078596	1.50
1	1	0.5	0.5	30																		B364023	278.50	279.68	1.535			VA05078596	1.18
0																						B364024	279.68	280.42	0.070			VA05078596	0.74
0																						B364025	280.42	281.12	0.099			VA05078596	0.70
0																						B364026	281.12	282.23	0.094			VA05078596	1.11
1	1	0.4	0.4	30																		B364027	282.23	283.46	0.046			VA05078596	1.23
1	4	0.5	0.5	30																									
6	1	1.0	2.5	30	45					1.0	2.0		0.1									B364028	283.46	284.79	0.158			VA05078596	1.33
6	1	1.0	2.5	30	45					1.0	2.0		0.1									B364029	283.46	284.79	0.200	PD/CA		VA05078596	1.33
																						B364030	STANDARD 6F		2.050	6F		VA05078596	
2	1	0.5	0.9	30							2.0	0.1										B364031	284.79	285.51	0.020			VA05078596	0.72
1	1	0.3	0.3	60														1.0				B364032	285.51	286.51	0.445			VA05078596	1.00

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 15 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		288.04	290.40	GND: Unaltered Grey GND; Moderate - abundant carbonate fractures; Carbonate in fractures have greenish hue - chlorite/sericite?						
10		290.40	295.15	GND: Clay altered grey GND - similar to interval 285.51 - 288.04m; Slightly less altered; Unaltered intervals of GND common (up to 25cm); Locally carbonate alteration occurs at 292.08 - 292.37m.				3		
10		295.15	298.70	GND: Grey GND with moderate clay alteration and slight carbonate alteration.				3	1	
10		298.70	306.93	GND: Sericite altered GND; Differing shades of green due to different amounts of carbonate; Hardness is consistent; @ 306.5-306.9m slight clay alteration (softer and lighter core); Slickenlines @ 306.78m with face at 70° and lines at 75° TCA.		4				
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar,, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	6	0.3	0.3	45						50.0																				
7	1	2.0	6.0	60																		B364033	286.51	288.04	**1.140**			VA05078596	1.53
4	1	1.0	3.0	50							0.1											B364034	288.04	289.56	**0.265**			VA05078596	1.52
3	1	1.0	1.5	50	45						1.0											B364035	289.56	290.40	**0.255**			VA05078596	0.84
																						B364036	BLANK		**<0.005**			VA05078596	
3	1	1.0	2.5	60																		B364037	290.40	291.08	**0.091**			VA05078596	0.68
1	1	1.2	1.2	55																		B364038	291.08	292.61	**0.073**			VA05078596	1.53
5	1	1.0	3.0	45																		B364039	292.61	294.13	**0.593**			VA05078596	1.52
2	1	1.4	2.0	45							1.0											B364040	294.13	295.15	**0.253**			VA05078596	1.02
3	1	1.0	2.0	50																		B364041	295.15	296.28	**0.159**			VA05078596	1.13
3	1	1.0	2.0	50																		B364042	295.15	296.28	**0.254**	DUP		VA05078596	1.13
4	1	4.5	6.0	45							0.1											B364043	296.28	297.18	**0.434**			VA05078596	0.90
1	6	0.5	0.5	60		2.5	q	5		25.0			15.0																	
2	1	2.0	3.0	60						1.0												B364044	297.18	298.70	**0.201**			VA05078596	1.52
9	1	4.0	12.0	60	45					1.0												B364045	298.70	300.23	**1.010**			VA05078596	1.53
1	6	2.0	2.0	50						25.0			50.0																	
2	1	3.0	4.0	60						0.1			0.1									B364046	300.23	301.75	**0.085**			VA05078596	1.52
0																						B364047	301.75	303.28	**0.123**			VA05078596	1.53
7	1	10.5	14.0	70		6.0	5	5		1.0	1.0		1.0									B364048	303.28	304.80	**0.996**			VA05078596	1.52
7	1	10.5	14.0	70		6.0	5	5		1.0	1.0		1.0									B364049	303.28	304.80	**1.025**	PD/CA		VA05078596	1.52
																						B364050	STANDARD 6F		**2.790**	6F		VA05078596	
7	1	5.0	8.5	70						1.0												B364051	304.80	306.32	**0.253**			VA05078596	1.52
																						B364052	306.32	306.93	**0.177**			VA05078596	0.61
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-303C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1139m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 5 - 10, 2005 | DATES LOGGING: August 21-26, 2005

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459958 NORTHING: 7099268

COORD SYSTEM: NAD 83: EASTING: 459839 NORTHING: 7099454

NAD 27 (CORRECTED for historic grid): EASTING: 459928 NORTHING: 7099278

SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 11.0 m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B364458 - B364536

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Aug-05

Lab Record #: VA05074738 Date Received: 2-Sept-05

Sample Sequence: B364537 - B364620

Requisition #: MASP448STRGOL.05Q Date Shipped: 2-Sept-05

Lab Record #: VA05078597 Date Received: 15-Sept-05

Sample Sequence: B364621 - B364699

Requisition #: MASP448STRGOL.05Q Date Shipped: 6-Sept-05

Lab Record #: VA05074738 Date Received: 21-Sept-05

Duplicates:	364462; 364482; 364502; 364522; 364542; 364562; 364582; 364602; 364622; 364642; 364662; 364682
Preparation Duplicate/ Check Assay:	364469; 364489; 364509; 364529; 364549; 364569; 364589; 364609; 364629; 364649; 364669; 364689
Standards:	364470 (1A); 364490 (6F); 364510 (6F); 364530 (4D); 364550 (3C); 364570 (1A); 364590 (4D); 364610 (7G); 364630 (5E); 364650 (2B); 364670 (7G); 364690 (5E)
Blanks:	364476; 364496; 364516; 364536; 364556; 364576; 364596; 364616; 364636; 364656; 364676; 364696

FROM	TO	LITHOLOGY
0.00	11.00	Casing
11.00	292.61	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
30.48	334.10	-50.20	0.10	1.10
109.72	332.00	-49.80	358.00	359.00
201.16	334.30	-48.00	0.30	1.30
292.59	337.10	-46.10	3.10	4.10

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: August 5 - 20, 2005	PAGE 1 of 12	
DRILL HOLE # : DG05-303C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 11.0	0.00	11.00	Casing						
10	11.00 - 292.61	11.00	18.29	GND: Weathered GND, 70% reduced to coarse sand and gravel texture; Competent core not longer than 8cm; Colour of clay is variable: at 12.0m it is orange-med brown, at 16.4m it is light yellowish orange and at 16.4m it is whitish yellow. Competent GND is oxidized to med brown but original texture still present; Hematite makes up 1-10% of veins in this section, 100% oxidized.	4			3	2	
10		18.29	24.08	GND: Sheeted quartz veins at 60° TCA crosscut by veinlets of limonite at 140° TCA; These veinlets have wide selvages - up to 4cm oxidized zones and appear to be later than the quartz veins. From 23.1 to 23.3m, rock is crumbly orangey brown oxidized clay-fine sand; Rest of the section is competent, solid GND with oxidation/alteration surrounding veins and veinlets; From 23.8 to 24.08m, competent core is completely oxidized and GND texture is erased to a uniform orangey brown.	3			1	1	
10		24.08	36.58	GND: Highly altered and oxidized GND; 70% clay to sand texture, crumbly, no structure seen, light to medium brown; Even within competent core, original GND is 70% erased to an aphanitic oxidized and sericitized state; Evidence of brittle-ductile shear movement (sinistral) of quartz veins and slickensides in oxidation products on fracture faces (py, hem).	4	3	2	3	3	
10		36.58	45.72	GND: Highly oxidized and moderately altered GND. All competent. From 43.6 - 45.7m rock is medium brown and aphanitic; GND Texture totally erased and sericitic alteration visible beneath.	3	2	1	1	2	
10		45.72	48.50	GND: Moderate alteration and oxidation zone; Competent core with GND texture (med grained).	3	1			1	
10		48.50	51.82	GND: Oxidized and carbonitic GND; Very broken up to sandy texture over 10%; Limonite (including calcite) fill fractures, brecciating rock into <10cm pieces; At least 2 generations of quartz veining: (1) 0.5cm at 40° contains >10% hematite, often weathered out, always rusty brown stained; and (2) >1cm, higher angle, usually broken up/brecciated by late limonite veining.	4	1		2	3	
10		51.82	64.01	GND: Little carbonate, less oxidation in competent core; GND texture preserved except in narrow selvages around frequent veins; Minor foliation development at 60° TCA and slickensides in sericite/carbonate on ~0° TCA fracture faces.	3				1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides									Oxidation					Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B364458	11.00	12.19	**0.810**			VA05074738	1.19
2	1	1.0	1.5	40		1.0	q/cb	2	3	2.0								5.0				B364459	12.19	13.72	**0.051**			VA05074738	1.53
0																						B364460	13.72	15.24	**0.052**			VA05074738	1.52
4	1	1.5	5.0	70		4.0	q/cb	5	4	0.1								5.0				B364461	15.24	16.76	**0.072**			VA05074738	1.52
4	1	1.5	5.0	70		4.0	q/cb	5	4	0.1								5.0				B364462	15.24	16.76	**0.054**	DUP		VA05074738	1.52
13	1	1.0	2.0	75	35	1.0	q/cb	2	4													B364463	16.76	18.29	**0.041**			VA05074738	1.53
2	3	1.0	1.4	45		2.0	q/cb	3	2																				
6	1	1.0	5.0	60		2.0	q/cb	4	4		4.0					0.1						B364464	18.29	19.81	**0.128**			VA05074738	1.52
5	1	1.0	5.0	60		2.0	q/cb	2	2		4.0											B364465	19.81	21.34	**0.091**			VA05074738	1.53
1	3	0.3	0.3	70		1.0	q/cb	4	0		2.0		5.0						4.0										
5	1	2.0	5.0	55		1.0	q/cb	3	4		4.0		2.0		2.0							B364466	21.34	22.86	**0.095**			VA05074738	1.52
1	1	0.5	0.5	50		0.5	q/cb	4	3		1.0				1.0			5.0				B364467	22.86	24.08	**0.643**			VA05074738	1.22
3	1	1.0	2.5	70	50	4.0	q/cb	3	4	0.1								5.0				B364468	24.08	25.00	**0.160**			VA05074738	0.92
3	1	1.0	2.5	70	50	4.0	q/cb	3	4	0.1								5.0				B364469	24.08	25.00	**0.142**	PD/CA		VA05074738	0.92
																						B364470	STANDARD 1A		**0.978**	1A		VA05074738	
4	3	2.0	7.0	60	45	2.0	q/cb	4	3	1.0								5.0				B364471	25.00	25.91	**0.068**			VA05074738	0.91
2	1	0.9	1.8	40	120	0.0				0.1					0.1			5.0				B364472	25.91	27.43	**0.162**			VA05074738	1.52
3	3	1.2	2.6	45		2.0	q/cb	4	4																				
1	1	1.0	1.0	30		0.0				0.0												B364473	27.43	28.96	**0.213**			VA05074738	1.53
4	3	2.0	4.5	40		2.0	q/cb	3	3	0.1							0.1					B364474	28.96	30.48	**0.342**			VA05074738	1.52
2	4	0.4	0.7	70		30.0	q/cb	5	2	0.0																			
3	1	1.0	3.0	75	30	0.0				2.0								5.0				B364475	30.48	32.00	**0.346**			VA05074738	1.52
2	3	1.0	2.0	30		2.0	q/cb	4	5	2.0								5.0				B364476	BLANK		**<0.005**			VA05074738	
0																						B364477	32.00	33.53	**0.162**			VA05074738	1.53
2	1	1.0	1.5	65		1.0	q/cb	1	4	0.1								5.0				B364478	33.53	35.05	**0.067**			VA05074738	1.52
3	1	0.5	1.5	5		1.0	q/cb	5	5	0.1								5.0				B364479	35.05	36.58	**0.146**			VA05074738	1.53
1	3	1.5	1.5	35		5.0	c	4	4	1.0					1.0			5.0											
4	1	1.2	3.5	40		2.0	q/k	4	4	2.0			1.0					5.0	3.0			B364480	36.58	38.10	**0.161**			VA05074738	1.52
1	1	1.0	1.0	40		2.0	q/k	3	3	2.0			2.0					5.0	3.0			B364481	38.10	39.62	**0.060**			VA05074738	1.52
4	3	0.6	3.2	50		3.0	q/k/cb	4	4				5.0						4.0										
1	1	1.0	1.0	40		2.0	q/k	3	3	2.0			2.0					5.0	3.0			B364482	38.10	39.62	**0.107**	DUP		VA05074738	1.52
4	3	0.6	3.2	50		3.0	q/k/cb	4	4				5.0						4.0										
3	1	3.0	5.0	50		2.0	q/s	3	1	2.0			0.1					5.0	3.0			B364483	39.62	41.15	**0.126**			VA05074738	1.53
1	3	1.3	1.3	45		1.0	q/cb	4	4	0.1					0.1			5.0											
2	1	0.5	1.0	40		1.0	q/s	3	1	2.0	0.1		0.1					5.0	5.0	2.0		B364484	41.15	42.67	**0.154**			VA05074738	1.52
1	3	0.3	0.3	40		1.0	q/cb	2	2						0.1														
3	1	2.5	5.0	40	30	32.0	q/s	4	5	5.0			8.0					5.0	5.0			B364485	42.67	44.20	**0.655**		Ox'd zone	VA05074738	1.53
3	1	0.5	1.5	40	25	4.0	s/q/cb	3	3	2.0								5.0				B364486	44.20	45.72	**0.101**			VA05074738	1.52
3	1	1.0	2.0	50	90	3.0	q	3	4				2.0									B364487	45.72	47.24	**0.078**			VA05074738	1.52
3	1	1.0	2.0	40	50	2.0	q/cb	3	2				0.1		0.1							B364488	47.24	48.50	**0.208**			VA05074738	1.26
3	1	1.0	2.0	40	50	2.0	q/cb	3	2				0.1		0.1							B364489	47.24	48.50	**0.119**	PD/CA		VA05074738	1.26
																						B364490	STANDARD 6F		**2.530**	6F		VA05074738	
4	1	0.5	2.0	40		4.0	q/cb	2	3													B364491	48.50	49.60	**0.428**		>10% hem, broken up	VA05074738	1.10
2	1	1.0	2.0							0.0																			
2	1	1.0	2.0	50		2.0	q	2	2													B364492	49.60	50.29	**0.184**			VA05074738	0.69
3	1	1.0	2.0	40		4.0	q	2	4	0.1								5.0				B364493	50.29	51.82	**0.192**			VA05074738	1.53
5	1	1.0	3.5	50		4.0	q/k	3	4	0.1								5.0				B364494	51.82	53.34	**0.124**			VA05074738	1.52
6	1	1.0	4.5	40		3.0	q/k	3	4	0.1							2.0	5.0				B364495	53.34	54.86	**0.099**		Moly	VA05074738	1.52

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2005 PAGE 3 of 12		
DRILL HOLE # : DG05-303C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		64.01	74.68	GND: Highly oxidized section; Limonite throughout GND matrix; Five zones infused with carb-rich limonite, reduced to clay gouge material, no wider than 20cm each; Qtz/carb and qtz veins have silicified selvages up to 2cm wide, moderately oxidized to rusty brown.	4	1		2	3	
10		74.68	86.87	GND: No clay gouge zones; Competent, moderately to highly oxidized. One pure clay seam at 84.70m (8cm wide), carb rich, effervesces; Few 'clear' unoxidized GND zones up to 20cm long, within competent core; Within frequent quartz veins, very little mineralization, but more oxidized hematite (up to 10%), and often weathered out, leaving vugs along the center of the veins.	3	1		1	1	
10		86.87	97.54	GND: Unoxidized GND slightly more prevalent in zones up to 40cm wide; No clay seams but core is still very broken up - to gravel in 10cm intervals (3 zones, 10cm wide); Quartz and quartz-carb veins still frequent; Quartz veins have solid boundaries while carb-rich veins are more gradational. Sulphides (oxidized py, scor'd aspy) are rare.	2	1			2	
10		97.54	104.56	GND: Altered to aphanitic, more sericite present; Selvages difficult to distinguish; Core is ~40% solid, partially silicified; Still very broken up on limonite-covered planes at ~40° and 140° TCA; Veinlets of limonite have wide, visible brown selvages up to 12cm wide.	3	2			3	
10		104.56	108.20	GND: Same aphanitic GND but more highly oxidized and broken up into <5cm pieces over 90% of the section.	4	1		1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 6 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B364496	BLANK		<0.005			VA05074738	
5	1	1.0	5.0	40		2.0	q/k/cb	3	4	0.1			4.0		1.0	0.1	5.0	1.0				B364497	54.86	56.39	0.075			VA05074738	1.53
2	3	1.0	1.5	60		8.0	q/cb	4	2				1.0				0.1		4.0										
2	1	0.6	0.9	30		3.0	q/cb	4	2				4.0		2.0							B364498	56.39	57.91	0.119			VA05074738	1.52
1	3	0.4	0.4	40		1.0	q/cb	4	1				5.0						3.0										
5	1	1.0	3.0	40	20	3.0	q/s	4	2		3.0		4.0				1.0		3.0			B364499	57.91	59.44	0.629			VA05074738	1.53
7	1	1.0	5.0	40	120	2.0	q/k/cb	4	3	0.1			0.1		1.0			5.0	1.0			B364500	59.44	60.96	0.215			VA05074738	1.52
3	3	0.3	0.9	35		2.0	q	3	2	0.1			4.0		0.1			5.0	4.0										
3	1	1.0	3.0	20		2.0	q	3	2	1.0			1.0					5.0				B364501	60.96	62.48	0.095			VA05074738	1.52
3	1	1.0	3.0	20		2.0	q	3	2	1.0			1.0					5.0				B364502	60.96	62.48	<0.005	DUP		VA05074738	1.52
5	1	2.0	5.5	40		3.0	q/cb/k	4	4	0.1			0.1					5.0	2.0			B364503	62.48	64.01	0.330			VA05074738	1.53
6	1	0.6	3.6	50	35	3.0	q/k.cb	3	4	0.1	1.0		3.0					5.0	1.0			B364504	64.01	65.53	0.122			VA05074738	1.52
4	1	2.0	4.5	50	60	0.0				0.1								5.0				B364505	65.53	67.06	0.281			VA05074738	1.53
4	1	1.0	4.0	40	60	2.0	q/k/cb	3	4	1.0								5.0				B364506	67.06	68.58	0.110			VA05074738	1.52
3	1	1.0	3.0	40		1.0	q	2	2	1.0								5.0				B364507	68.58	70.10	0.102			VA05074738	1.52
3	1	1.0	3.0	65		1.0	q/cb	3	2	2.0								5.0				B364508	70.10	71.63	0.062			VA05074738	1.53
1	3	0.5	0.5	40		1.0	q/cb	2	1				0.1						3.0										
3	1	1.0	3.0	65		1.0	q/cb	3	2	2.0								5.0				B364509	70.10	71.63	0.054	PD/CA		VA05074738	1.53
1	3	0.5	0.5	40		1.0	q/cb	2	1				0.1						3.0										
																						B364510	STANDARD 6F		2.660	6F		VA05074738	
2	1	0.6	1.2	40		1.0	q/cb	4	3	0.1								5.0				B364511	71.63	73.15	0.149			VA05074738	1.52
4	1	1.0	2.0	50	45	2.0	q/cb	4	2													B364512	73.15	74.68	0.294			VA05074738	1.53
4	1	1.0	4.0	50	35	2.0	q/cb	2	3	0.1					0.1			5.0				B364513	74.68	76.20	0.620			VA05074738	1.52
3	1	1.0	3.0	35		2.0	q/cb/s	3	3	2.0			4.0				0.1	5.0	4.0			B364514	76.20	77.72	0.992		Moly	VA05074738	1.52
4	1	2.0	5.0	35		2.0	q/s/cb	3	3	3.0			5.0				0.1	5.0	4.0			B364515	77.72	79.25	1.745			VA05074738	1.53
																						B364516	BLANK		<0.005			VA05074738	
5	1	1.5	4.5	30		1.0	q/cb	4	3	1.0								5.0				B364517	79.25	80.77	0.668			VA05074738	1.52
1	4	0.4	0.4	50		3.0	q/cb	2	4	5.0								5.0											
7	1	2.0	7.0	45		2.0	q/s/cb	3	3								1.0					B364518	80.77	82.30	0.734			VA05074738	1.53
5	1	1.3	4.5	20	45	3.0	q/s/cb	4	4	3.0								4.0				B364519	82.30	83.82	0.189			VA05074738	1.52
2	1	0.5	1.0	30		2.0	q	2	3	0.1								5.0				B364520	83.82	85.34	0.223			VA05074738	1.52
4	1	2.0	8.0	30		2.0	q/s/cb	4	3				5.0						4.0			B364521	85.34	86.87	0.424			VA05074738	1.53
4	1	2.0	8.0	30		2.0	q/s/cb	4	3				5.0						4.0			B364522	85.34	86.87	0.396	DUP		VA05074738	1.53
3	1	1.3	3.0	50		2.0	q	5	5	1.0								5.0				B364523	86.87	88.39	4.170			VA05074738	1.52
5	1	1.2	5.0	30	60	2.0	q/k	5	3	1.0					0.1			5.0				B364524	88.39	89.92	1.060			VA05074738	1.53
7	1	0.5	3.5	40	50	2.0	q/k/cb	4	4	3.0					0.1			5.0				B364525	89.92	91.44	0.149			VA05074738	1.52
4	1	0.5	2.0	50		2.0	q/k/cb	4	5	0.1								5.0				B364526	91.44	92.96	0.515			VA05074738	1.52
1	1	1.0	1.0	40		3.0	q/cb	4	3													B364527	92.96	94.49	1.415			VA05074738	1.53
4	3	0.4	2.4	40		2.0	q/s/cb	3	1				5.0						4.0										
1	1	0.5	0.5	40		6.0	q/s/cb	3	4						0.1							B364528	94.49	96.01	0.068			VA05074738	1.52
1	3	0.5	0.5	30		2.0	q/cb	2	5	0.1					0.1			5.0											
1	1	0.5	0.5	40		6.0	q/s/cb	3	4						0.1							B364529	94.49	96.01	0.080	PD/CA		VA05074738	1.52
1	3	0.5	0.5	30		2.0	q/cb	2	5	0.1					0.1			5.0											
																						B364530	STANDARD 4D		0.464	4D		VA05074738	
1	1	0.6	0.6	30		2.0	q/s/cb	4	3	0.1					0.1			5.0				B364531	96.01	97.54	0.037			VA05074738	1.53
1	1	2.0	2.0	30						0.1								5.0				B364532	97.54	99.06	0.187			VA05074738	1.52
3	1	2.0	2.8	40		10.0	q	3	2	2.0								5.0				B364533	99.06	100.58	4.310			VA05074738	1.52
1	4	0.4	0.4	50		6.0	q/s/cb	2	3													B364534	100.58	101.66	0.073			VA05074738	1.08
0																						B364535	101.66	103.12	0.264			VA05074738	1.46
																						B364536	BLANK		<0.005			VA05074738	
0																						B364537	103.12	104.56	0.167			VA05078597	1.44
0																						B364538	104.56	106.13	0.327			VA05078597	1.57
0																						B364539	106.13	106.88	0.082			VA05078597	0.75
0																						B364540	106.88	108.20	0.132			VA05078597	1.32

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2006	PAGE 5 of 12								
DRILL HOLE # : DG05-303C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence							
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41										
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93										

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		108.20	112.78	GND: Same aphanitic GND, silicified and almost completely oxidized, although 100% of section is competent; As for veins, only a few small ones are visible; Oxidized hematite (and pyrite?) seen disseminated through section, so perhaps qtz veins contributed to silicification and were incorporated into GND.	3	2			1	
10		112.78	118.87	GND: Same aphanitic GND; More altered and sheared and broken up, especially from 113.65m to 114.6m, where shear and sericite is intense; Also at 118.55m a 15cm zone of fault breccia; Jointing at 25° and 100° TCA.	3	3		1	3	
10		118.87	132.59	GND: Unaltered GND (50%) with quartz veins with oxidized and/or silicified selvages (50%); Decreased limonite; 80% competent core (pieces >10cm); Common sheeted veins; Sulphides within (py, po, aspy) are oxidized up to 100% at least 50%; Molybdenite appears as soft, bluish-silver, rounded pieces within or beside quartz veins; Quartz veins have clear boundaries and obvious selvages, mostly silicified within sericite alteration as well, often limonitic.	2	1			1	
10		132.59	139.78	GND with numerous 1mm-1cm quartz veins; Selvages up to 10cm, are silicified and sericitic usually with rusty oxidation and carbonate.	2	2		1	2	
10		139.78	140.83	All oxidized and sericitized; GND texture 90% reduced to aphanitic. One quartz vein with strongly-defined selvage.	4	3			2	
		140.83	144.78	GND: Big, frequent quartz veins with oxidized selvages; Limonite still on fracture planes and throughout GND matrix; Slickensides in sericite on low angle fracture faces	3	1			3	
10		144.78	146.86	GND: Completely oxidized and broken up to coarse gravel/sand-size fragments; Colour is pale to medium brown; No competent core but gravel chunks appear as highly sericitized GND or quartz eyes.	5	3		3	4	
10		146.86	159.43	GND: Competent core with a lot less limonite, only thinly distributed along veinlets/fracture faces. Milky white to pale grey quartz veins with ox'd, ser'd, silicified selvages. Minor sulphides are mostly oxidized. Beginning around 150m (+/- 20cm), alteration is more pervasive and GND texture reduced to aphanitic with only qtz eyes preserved (20% rounded, 2mm grains), Other 80% is oxidized/limonite-stained and/or sericitized to pale green; From 152.0 - 156.0m rock is 70% competent and has ~5-10 cm bands of different alteration types; These bands are oriented at ~20°-50° TCA; Sericite, clay rich and oxidized competent GND make up this section. Colourful; First view unaltered GND at 156.0m; Still has branching veinlets of limonite throughout, crumbly brecciated gouge at 156.85m for 15cm; 2 more before 159.43m.	4	3	1	2	4	
10		159.43	161.79	GND: Zone of extreme alteration but minimal oxidation; Remnant bt texture and qtz preserved from original GND, but 90% texture is massive and speckled with oxidized carbonate, up to 3mm in diameter; Veins are relicts, bent, with little to no selvage.	2	5	2	1	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval					
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.3	0.3	40		1.0	q/cb	3	2													B364541	108.20	109.73	**0.070**			VA05078597	1.53
1	1	0.3	0.3	40		1.0	q/cb	3	2													B364542	108.20	109.73	**0.067**	DUP		VA05078597	1.53
3	1	0.3	0.9	40		1.0	q/cb	3	3	0.1								5.0	2.0			B364543	109.73	111.25	**0.107**			VA05078597	1.52
1	1	0.3	0.3	40		2.0	q/s	4	1				1.0						4.0			B364544	111.25	112.78	**0.707**			VA05078597	1.53
1	1	0.3	0.3	40		1.0	q/cb	5	2				0.1									B364545	112.78	114.30	**0.160**			VA05078597	1.52
1	1	0.7	0.7	35		4.0	q/cb/s	3	2	0.1			0.1					5.0	5.0			B364546	114.30	115.82	**0.416**			VA05078597	1.52
2	1	1.0	1.5	40		8.0	q/s	4	2								0.1					B364547	115.82	117.35	**0.056**		Moly	VA05078597	1.53
5	1	1.5	4.5	35		4.0	q/cb/s	2	2								0.1					B364548	117.35	118.87	**6.500**			VA05078597	1.52
5	1	1.5	4.5	35		4.0	q/cb/s	2	2								0.1					B364549	117.35	118.87	**4.670**	PD/CA		VA05078597	1.52
																						B364550	STANDARD 3C		**0.096**	3C		VA05078597	
5	1	1.0	5.0	50		4.0	q/cb/s	4	2				3.0						2.0			B364551	118.87	120.40	**0.706**			VA05078597	1.53
5	1	1.0	4.0	50		4.0	q/cb/s	4	2	0.1								5.0				B364552	120.40	121.92	**1.495**			VA05078597	1.52
6	1	1.0	5.0	50		2.0	q/cb/s	4	3	1.0			1.0					5.0	2.0			B364553	121.92	123.44	**0.749**			VA05078597	1.52
7	1	1.0	4.5	40		4.0	q/s	3	1	0.1	2.0		0.1					1.0	3.0			B364554	123.44	124.97	**5.330**			VA05078597	1.53
4	1	1.0	3.0	30		3.0	q/cb/k	2	1	0.1	3.0		0.1					1.0	3.0			B364555	124.97	126.49	**1.250**			VA05078597	1.52
3	3	0.3	0.9	30		2.0	s/cb	2	1																				
																						B364556	BLANK		**<0.005**			VA05078597	
3	1	1.0	3.0	50		2.0	q/s	4	1	2.0								2.0				B364557	126.49	128.02	**0.226**			VA05078597	1.53
7	1	1.0	5.5	40	50	2.0	q/cb	4	2	1.0							3.0	1.0	4.0			B364558	128.02	129.54	**2.330**		Scor, moly, ox py	VA05078597	1.52
2	1	1.0	1.5	45		2.0	q/s	4	1	2.0					0.1		1.0	2.0				B364559	129.54	131.06	**0.152**			VA05078597	1.52
7	3	0.3	2.1	40		1.0	q/cb	3	1																				
6	1	1.0	5.0	40		4.0	q/s	5	1										3.0			B364560	131.06	132.59	**0.946**			VA05078597	1.53
3	1	1.0	3.0	30	60	1.0	q/cb	3	2	1.0								1.0				B364561	132.59	134.11	**4.640**			VA05078597	1.52
3	1	1.0	3.0	30	60	1.0	q/cb	3	2	1.0								1.0				B364562	132.59	134.11	**9.050**	DUP		VA05078597	1.52
6	1	2.0	6.5	45	30	10.0	q/cb	4	4	1.0							0.1	1.0				B364563	134.11	135.64	**1.350**		moly	VA05078597	1.53
5	1	1.0	3.5	40		2.0	q/s/cb	3	2	0.1			4.0		0.1			5.0	4.0			B364564	135.64	137.16	**1.250**			VA05078597	1.52
5	1	1.0	4.0	35		6.0	q/s/cb	3	1	0.1	3.0							5.0				B364565	137.16	138.68	**0.608**		Cu coloured po	VA05078597	1.52
1	3	0.3	0.3	40		2.0	q/cb/s	3	0	0.1	q																		
3	1	1.0	3.0	40		4.0	q/s	3	2	1.0					2.0			5.0	5.0			B364566	138.68	139.78	**0.650**			VA05078597	1.10
1	3	0.3	0.3	55		1.0	cb	2	3																				
1	1	1.0	1.0	40		3.0	q/cb	5	3	0.1							0.1	5.0				B364567	139.78	140.83	**0.909**			VA05078597	1.05
5	1	1.0	3.0	40		3.0	q/s	3	1		2.0							5.0				B364568	140.83	141.73	**0.644**			VA05078597	0.90
5	1	1.0	3.0	40		3.0	q/s	3	1		2.0							5.0				B364569	140.83	141.73	**1.330**	PD/CA		VA05078597	0.90
																						B364570	STANDARD 1A		**1.015**	1A		VA05078597	
8	1	1.0	5.0	40		4.0	q/cb	4	2	1.0	2.0				0.1			5.0				B364571	141.73	143.26	**2.740**			VA05078597	1.53
6	1	2.5	9.0	40	20	2.0	cb/q	3	3				2.0						5.0			B364572	143.26	144.78	**1.115**			VA05078597	1.52
1	3	2.0	2.0	30		2.0	cb/q	3	3				4.0						5.0										
0																						B364573	144.78	145.80	**1.415**			VA05078597	1.02
0																						B364574	145.80	146.86	**0.672**			VA05078597	1.06
5	1	1.3	5.0	30	15	8.0	q/s	5	1	2.0	2.0		3.0					3.0				B364575	146.86	147.83	**1.025**			VA05078597	0.97
																						B364576	BLANK		**<0.005**			VA05078597	
6	1	1.5	5.5	60	25	4.0	q/cb/s	4	2	1.0								5.0				B364577	147.83	149.35	**0.946**			VA05078597	1.52
3	1	1.0	3.0	30		2.0	q/cb/s	2	4	0.1								5.0				B364578	149.35	150.88	**1.165**			VA05078597	1.53
1	3	0.5	0.5	40		2.0	q/cb/s	3	4	1.0								5.0											
4	1	2.0	5.3	35	10	10.0	q/s/cb	4	4	2.0			1.0					0.0	0.0			B364579	150.88	152.40	**2.900**			VA05078597	1.52
7	1	0.5	3.5	50		4.0	q/cb/s	5	5	0.1								5.0				B364580	152.40	153.92	**1.360**			VA05078597	1.52
4	1	2.0	5.0	65		4.0	q/cb/s	5	3		2.0						0.1					B364581	153.92	155.45	**0.669**			VA05078597	1.53

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2005	PAGE 7 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.79	165.27	GND: Same sericitized GND except highly oxidized as well; Limonite throughout, so rock is broken up into gravel in 2 zones: 30cm at 163.9m and 15cm at 164.8m; At 162.75m - 163.0m, banding of greenish dark grey clay with white carbonate in between, at 80° TCA; Overall color is strong orangey brown masking bluish green micaceous rock.	5	5	1	2	4	
10		165.27	170.39	GND: GND texture visible over 75% of section, not oxidized and minor alteration; Rock is weakened by influx of carbonate and sericite (no veins associated) at 167.5 - 167.64m; Last 50cm is all rearranged and alt'd GND, surrounding relict quartz vein.	2	2	1	1	2	
10		170.39	195.07	GND: Large zone of silicified and sericitized GND; Texture is cryptocrystalline except for ~10% (secondary?) biotite, up to 2mm in diameter; Frequent qtz, carb and qtz/carb veins produce carb-rich selvages which appear as lighter green than the surrounding deep blue-green rock matrix; The whole section is silicified, so is probably a selvage of the sheeted veins itself, but cannot be separated between veins here; Selvages are carb'd, ser'd and sil'd; Super carb-rich zone at 175.26 - 175.50m; Softened and broken into <10cm pieces; From 189.55 - 195.07m is all "selvage", carb-rich and weakened GND, no more silicified deep blue-green.	1	5	2	1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	3	1.0	1.0	65		6.0	s/cb	5	3	2.0								5.0											
4	1	2.0	5.0	65		4.0	q/cb/s	5	3		2.0						0.1					B364582	153.92	155.45	**0.698**	DUP		VA05078597	1.53
1	3	1.0	1.0	65		6.0	s/cb	5	3	2.0								5.0											
2	1	4.0	6.0	65	30	20.0	q/s/cg/chl	5	2	10.0								3.0				B364583	155.45	156.97	**1.165**			VA05078597	1.52
2	1	0.6	1.2	40		4.0	q/cb/s	3	4	0.1				0.1			0.1	4.0				B364584	156.97	158.50	**0.399**			VA05078597	1.53
2	1	2.0	4.0	70		2.0	q/cb/s	4	3	4.0								5.0				B364585	158.50	159.43	**1.175**			VA05078597	0.93
2	1	1.0	2.0	40		2.0	q	2	0													B364586	159.43	160.61	**0.094**			VA05078597	1.18
2	1	1.0	2.0	50		0.0				0.1								5.0				B364587	160.61	161.79	**0.983**			VA05078597	1.18
0																						B364588	161.79	163.07	**0.079**			VA05078597	1.28
0																						B364589	161.79	163.07	**0.086**	PD/CA		VA05078597	1.28
																						B364590	STANDARD 4D		**0.460**	4D		VA05078597	
1	1	2.0	2.0			0.0				0.0												B364591	163.07	164.59	**1.650**		Quartz piece <1cm in diam	VA05078597	1.52
0																						B364592	164.59	165.27	**0.354**			VA05078597	0.68
0																						B364593	165.27	166.12	**0.036**			VA05078597	0.85
3	1	3.0	6.0	45		2.0	q	2	2				1.0		2.0		0.1		2.0			B364594	166.12	167.64	**0.325**		moly	VA05078597	1.52
4	1	2.5	6.0	50	40	1.0	q	4	0		20.0											B364595	167.64	169.16	**0.632**			VA05078597	1.52
1	6	0.4	0.4	50		1.0	cb/q	5	0		70.0		10.0						5.0										
																						B364596	BLANK		**<0.005**			VA05078597	
3	1	1.0	3.0	40		0.0																B364597	169.16	170.39	**0.135**			VA05078597	1.23
1	1	2.0	2.0	40		50.0	q/cb/chl	5	2	5.0								5.0											
6	1	2.0	7.0	60	50	8.0	cb/s/chl	4	1	3.0								2.0				B364598	170.39	171.30	**0.453**			VA05078597	0.91
2	1	1.5	2.2	50	70	4.0	cb/s	4	0	0.1								5.0				B364599	171.30	172.21	**0.234**			VA05078597	0.91
2	3	0.5	1.0	45		4.0	cb/s/chl	4	0																				
2	1	2.5	3.5	50	70	40.0	cb/s	5	1	5.0								5.0				B364600	172.21	173.74	**0.090**			VA05078597	1.53
2	1	4.0	8.0	80		40.0	cb/s	5	5	4.0								4.0				B364601	173.74	175.26	**0.360**			VA05078597	1.52
2	1	4.0	8.0	80		40.0	cb/s	5	5	4.0								4.0				B364602	173.74	175.26	**1.455**	DUP		VA05078597	1.52
5	1	6.0	16.0	70		4.0	cb/s	5	1		3.0		1.0									B364603	175.26	176.78	**0.626**			VA05078597	1.52
4	1	2.5	6.0	50		4.0	cb/s	5	0	5.0	2.0							3.0				B364604	176.78	178.31	**2.390**			VA05078597	1.53
1	4	0.5	0.5	45		40.0	cb/q	5	0																				
5	1	4.0	8.5	55		8.0	cb/s/chl	5	1	2.0	3.0		0.1									B364605	178.31	179.83	**2.880**			VA05078597	1.52
1	6	0.5	0.5	40		1.0	cb/q	4	1		40.0	10.0	20.0					4.0											
7	1	8.0	14.0	50		50.0	cb/s/chl	5	0	3.0								3.0				B364606	179.83	181.36	**0.723**			VA05078597	1.53
2	1	0.8	1.5	50	70	4.0	cb/s	5	0	0.1	2.0							4.0				B364607	181.36	182.88	**0.058**			VA05078597	1.52
4	4	0.3	1.2	50	15	1.0	cb	2	0																				
6	1	1.0	4.7	50		22.0	cb/s	5	0		1.0											B364608	182.88	184.40	**0.945**			VA05078597	1.52
2	4	0.3	0.6	50		4.0	cb/s	5	0																				
6	1	1.0	4.7	50		22.0	cb/s	5	0		1.0											B364609	182.88	184.40	**0.761**	PD/CA		VA05078597	1.52
2	4	0.3	0.6	50		4.0	cb/s	5	0																				
																						B364610	STANDARD 7G		**4.290**	7G		VA05078597	
2	1	1.2	2.0	50		4.0	cb/s	5	2													B364611	184.40	185.93	**3.220**		Low angle vein selvage width of core.	VA05078597	1.53
1	6	0.3	0.3	0	10		cb	5	2	100.0								5.0											
3	1	1.2	3.3	50		2.0	cb/s	5	0	0.1								5.0				B364612	185.93	187.45	**0.202**			VA05078597	1.52
5	1	3.0	8.5	60	50	8.0	cb/s	5	0	0.1								5.0				B364613	187.45	188.98	**1.680**			VA05078597	1.53
2	4	0.6	0.4	60	50	8.0	cb/s	5	0																				
3	1	3.0	5.0	60	50	20.0	cb/s	5	0	2.0								2.0				B364614	188.98	190.50	**1.645**			VA05078597	1.52
5	1	5.0	7.5	40		40.0	cb/s	5	1	0.1								5.0				B364615	190.50	192.02	**0.240**			VA05078597	1.52
																						B364616	BLANK		**<0.005**			VA05078597	
4	1	2.0	5.0							0.1												B364617	192.02	193.55	**1.140**			VA05078597	1.53
1	6	1.0	1.0	25		10.0	cb/chl/s	5	1	100.0								5.0											
2	1	1.0	2.0	60						0.1								5.0				B364618	193.55	195.07	**7.410**			VA05078597	1.52
2	4	0.4	0.8	60		0.0																							
2	6	1.0	1.5	50		10.0	cb/chl/s	5		100.0								5.0											

DRILL LOG LEGEND P1	DATE: August 5 - 20, 2006	PAGE 4 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		195.07	204.22	GND: From 195.07 - 196.6m is a gradation from sericitized and silicified GND to unalt'd GND between veins. After this, veins are similarly frequent and have carb/ser selvages but are separated by less alt'd GND instead of deep blue-green silicified; This "less altered" GND has minor sericite alteration, such that texture is 80% preserved, outside of selvages, but rock is still sericite-rich; Slickensides at 200m.	1	4		1	3	
10		204.22	208.79	GND: Carb-rich GND, weakened and broken up, especially from 205.74-208.5m (middle of section); Pieces ≤10cm long, not full core diameter. In this zone as well are slickensides in fresh pyrite and sericite, on low angle fractures, 20° TCA, slickensides to 80°.	2	4	1	2	4	
10		208.79	217.93	GND: Carb still prevalent but not as much as above; Numerous large quartz veins (up to 7cm) with sulphides both within and concentrated at boundaries of veins; Larger and stronger selvage alteration associated with increased sulphide content in/beside veins; At 220m, a 6cm quartz vein is at 5° TCA, so is seen across ~1m interval; Sulphides are minimal (~2% po and trace ox'd py); Bt alt'n within, 5%.	2	4	1	1	2	
10		217.93	228.60	GND: Unaltered GND with slightly fewer and smaller quartz veins with well-defined selvages; Veins in 2 orientations (0-5° and 50-60°) appear to be coeval, or high angle offset low angle veins, slightly.		2	1		2	
10		228.60	243.84	GND: More weakened by carb veinlets in random orientations, so broken up to crumbly in spots up to 30cm long; Between 241.0 and 242.6m, low angle quartz veins contain a high concentration of carbonate and chlorite (up to 50%).		2	1	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Phm Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorolite	biotite	other		From	To					
2	1	0.5	1.0	60		1.0	q	3	0		3.0											B364619	195.07	196.60	**0.166**			VA05078597	1.53
3	1	2.5	5.5	60	50	10.0	cb/s	5	0		2.0											B364620	196.60	198.12	**0.070**			VA05078597	1.52
3	3	1.0	3.0	60		8.0	c/s	5	0																				
6	1	2.0	7.0	65	30	10.0	cb/s	4	0	6.0	4.0		1.0					4.0				B364621	198.12	199.64	**0.093**			VA05080698	1.52
6	1	2.0	7.0	65	30	10.0	cb/s	4	0	6.0	4.0		1.0					4.0				B364622	198.12	199.64	**0.152**	DUP		VA05080698	1.52
6	1	1.5	6.0	50	70	10.0	cb/s	4	1	4.0	3.0											B364623	199.64	201.17	**0.203**			VA05080698	1.53
6	1	2.0	9.0	40	75	20.0	cb/s	5	0	1.0								5.0				B364624	201.17	202.69	**0.175**			VA05080698	1.52
7	1	1.2	5.0	30	40	6.0	cb/s	5	1	1.0								5.0				B364625	202.69	204.22	**0.696**			VA05080698	1.53
1	4	0.4	0.4	45		24.0	cb/s	5	0	5.0								5.0											
3	1	3.0	9.0	30	15	20.0	cb/s	5	1	8.0								4.0				B364626	204.22	205.74	**0.266**			VA05080698	1.52
1	6	0.6	0.6	75		2.0	cb	5	3	100.0								5.0											
2	4	0.5	1.0	30		8.0	s/cb	5	2																				
4	1	2.0	4.5	55		24.0	s/cb	5	1	4.0								3.0				B364627	205.74	207.26	**0.078**		Slicks in fresh pyrite	VA05080698	1.52
5	1	4.0	15.0	55	15	30.0	cb/s	5	2	4.0	3.0							5.0				B364628	207.26	208.79	**0.391**			VA05080698	1.53
5	1	4.0	15.0	55	15	30.0	cb/s	5	2	4.0	3.0							5.0				B364629	207.26	208.79	**0.333**	PD/CA		VA05080698	1.53
																						B364630	STANDARD 5E		**1.486**	5E		VA05080698	
5	1	2.0	6.0	50	35	8.0	cb/s	5	0	2.0	4.0							4.0				B364631	208.79	210.31	**0.062**		Ox'd pyrite along margins	VA05080698	1.52
2	4	0.3	0.6	45		4.0	cb/s/q	5		10.0								5.0											
5	1	7.0	10.0	65	35	40.0	cb/s/q	5	1	12.0								3.0				B364632	210.31	211.84	**0.327**			VA05080698	1.53
7	1	1.0	6.5	50	40	8.0	cb/s	5	0	3.0	5.0							5.0				B364633	211.84	213.36	**0.243**			VA05080698	1.52
3	1	2.0	3.5	60		10.0	cb/s	5	1	2.0								3.0				B364634	213.36	214.12	**0.197**			VA05080698	0.76
3	1	7.0	10.0	60	80	20.0	cb/s	5	1	15.0								3.0				B364635	214.12	214.88	**0.647**			VA05080698	0.76
																						B364636	BLANK		**<0.005**			VA05080698	
1	6	8.0	8.0	60							100.0							5.0				B364637	214.88	216.41	**0.430**			VA05080698	1.53
5	1	3.0	10.0	55	35	6.0	cb/s	3	0	2.0	3.0		2.0					5.0											
6	1	1.0	5.0	45	60	1.0	q/s	3	0		2.0											B364638	216.41	217.93	**0.245**			VA05080698	1.52
2	3	0.5	1.0	50		2.0	cb/s/q	4	1	0.1			0.1					5.0											
7	1	2.0	9.0	20	40	2.0	cb/q/s	3	0	0.1	2.0							5.0	5.0			B364639	217.93	219.46	**0.303**			VA05080698	1.53
3	1	6.0	9.0	40	5	2.0	s/q	5	0	1.0	2.0							5.0		5.0		B364640	219.46	220.98	**0.673**		Unaltered po	VA05080698	1.52
7	1	10.0	24.0	25	50	3.0	q/s/cb	4	0	2.0	5.0	0.1						1.0				B364641	220.98	222.50	**0.470**			VA05080698	1.52
7	1	10.0	24.0	25	50	3.0	q/s/cb	4	0	2.0	5.0	0.1						1.0				B364642	222.50	222.50	**0.096**	DUP		VA05080698	0.00
6	1	3.0	7.5	50	5	3.0	cb/s	4			2.0								5.0	3.0		B364643	222.50	224.03	**0.197**			VA05080698	1.53
6	1	1.2	4.0	50		4.0	cb/s/chl	4	0		4.0								5.0			B364644	224.03	225.55	**0.526**			VA05080698	1.52
7	1	1.0	4.0	55	30	2.0	cb/q/s	4			8.0								3.0	2.0		B364645	225.55	227.08	**0.087**			VA05080698	1.53
6	1	1.0	5.0	70	20	10.0	s/chl/cb	5	0	3.0	0.1							5.0		0.1		B364646	227.08	228.60	**0.431**			VA05080698	1.52
4	1	1.0	3.5	40		1.0	cb/q/s	2	0		2.0								2.0	2.0		B364647	228.60	230.12	**0.223**			VA05080698	1.52
4	1	1.5	4.5	50	70	1.0	q	3	1		6.0								5.0	4.0		B364648	230.12	231.65	**0.122**			VA05080698	1.53
1	3	0.5	0.5	45		2.0	q/cb	3	0		10.0																		
4	1	1.5	4.5	50	70	1.0	q	3	1		6.0								5.0	4.0		B364649	230.12	231.65	**0.108**	PD/CA		VA05080698	1.53
1	3	0.5	0.5	45		2.0	q/cb	3	0		10.0																		
																						B364650	STANDARD 2B		**3.040**	2B		VA05080698	
4	1	3.0	5.5	60	20	4.0	cb/s/q	4	0		3.0	0.1								1.0		B364651	231.65	233.17	**0.493**			VA05080698	1.52
1	4	1.0	1.0	45		6.0	cb/s/q	3	0		10.0																		
3	1	1.0	3.0	50		4.0	cb/s/chl/q	4			5.0		5.0						5.0	2.0		B364652	233.17	234.70	**0.215**			VA05080698	1.53
2	4	0.3	0.6	35	0	0.5	cb	4																					
5	1	3.0	6.5	30	60	2.0	q/cb/chl	4	0	2.0	0.1							5.0	2.0			B364653	234.70	236.22	**0.856**			VA05080698	1.52
5	3	0.3	1.5	45		2.0	cb/chl	5	0		0.1								2.0										
6	1	4.0	11.0	60	45	10.0	s/chl/cb	5	0	1.0	10.0	0.1	2.0									B364654	236.22	237.74	**0.940**			VA05080698	1.52
2	4	0.2	0.4	60		4.0	cb/s	4			4.0		2.0																
2	1	1.2	2.2	60		2.0	q/chl	4	0		10.0											B364655	237.74	239.27	**0.180**			VA05080698	1.53
2	4	1.0	2.0	30	15	2.0	cb	3	1																				
																						B364656	BLANK		**<0.005**			VA05080698	
2	1	1.5	2.7	50		0.5	q/cb	4	0		3.0		6.0									B364657	239.27	240.79	**0.509**			VA05080698	1.52

DRILL LOG LEGEND P1	DATE: August 5 - 20, 2005	PAGE 11 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		243.84	259.08	GND: 95% unalt'd GND; Few quartz veins have <5cm selvages; Sericite, chlorite and silicification alteration moderate within; Competent core except where moderate carbonate intrudes on veinlets at random angles TCA: from 246.89m - 247.07m and 242.9 - 243.0m. This section contains two types of quartz veins with the same mineralization (~5% po); Thin (0.5cm) veins at 50-60° TCA with 2-3cm selvages, and 1.5-2cm veins with little or no selvages, generally at 50° TCA; Each section usually contains 1 wide one and 3-4 of the smaller type.		1	1		1	
10		259.08	271.27	GND: Somewhat more alt'd and broken up core; Evidence of movement from 259.5 - 260.0m; Carb, chl and ser rich zone and one qtz vein moved 1cm, sinistrally; Other than these zones of alt'n, rock is unaltered GND with ~2-3 carb-rich qtz veins per metre.	1	2	2		2	
10		271.27	280.42	GND: Moderate carb influx weakens otherwise unalt'd GND; 4-6 quartz veins per metre. Whole section is crumbly and broken up; Carb veinlets at low angles TCA cause breakage.		3	2	1	3	
10		280.42	292.61	Unalt'd, competent GND. 5mm to 2cm qtz veins still frequent: ~5 veins per metre.Three zones of sericitic/chloritic/minor carb alt'n: from 285.40-286.10m, from 286.8-286.9m, and from 287.50-288.04m. Last sample contains 2 types of qtz veins - one 3cm vein contains sulphides, one does not.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3	1.0	2.0	0	15	26.0	cb	3			15.0								10.0			B364658	240.79	242.32	**3.620**			VA05080698	1.53
1	1	5.0	5.0	30		40.0	cb/s	3			5.0								5.0										
6	1	25.0	6.0	45	15	1.0	cb/s	3	1	5.0	4.0							5.0				B364659	242.32	243.84	**1.225**			VA05080698	1.52
4	1	1.0	3.0	50		4.0	chl/q	4	0		5.0		0.1									B364660	243.84	245.36	**0.124**			VA05080698	1.52
5	1	2.0	5.5	50		4.0	cb/chl	5	0	0.1	2.0		0.1									B364661	245.36	246.89	**0.049**			VA05080698	1.53
5	1	2.0	5.5	50		4.0	cb/chl	5	0	0.1	2.0		0.1									B364662	245.36	246.89	**0.098**	DUP		VA05080698	1.53
4	1	1.0	1.8	50	40	3.0	cb/s	4	0		5.0		0.1						4.0			B364663	246.89	248.41	**0.276**			VA05080698	1.52
5	1	2.0	4.5	50	60	1.0	q/cb	3	0		5.0											B364664	248.41	249.94	**0.079**			VA05080698	1.53
6	1	1.5	5.0	50	60	2.0	s/chl	3	0		5.0	0.1	1.0						1.0			B364665	249.94	251.46	**0.058**			VA05080698	1.52
3	1	0.8	2.0	40	20	1.0	q/cb	2	0		5.0		0.1						5.0			B364666	251.46	252.98	**0.152**			VA05080698	1.52
4	1	1.5	2.5	50		2.0	q/cb/chl	3	0		5.0		0.1						3.0			B364667	252.98	254.51	**2.150**			VA05080698	1.53
2	3	0.2	0.4	50		2.0	cb/chl	2	0																				
3	1	4.3	5.5	45	60	2.0	cb/s	3	0		5.0	0.1										B364668	254.51	256.03	**1.610**			VA05080698	1.52
3	1	4.3	5.5	45	60	2.0	cb/s	3	0		5.0	0.1										B364669	254.51	256.03	**1.195**	PD/CA		VA05080698	1.52
																						B364670	STANDARD 7G		**4.520**	7G		VA05080698	
3	1	1.0	2.3	60	20	10.0	cb/chl	3	0		4.0		0.1						5.0			B364671	256.03	257.56	**0.606**		Po in selvage	VA05080698	1.53
1	1	9.0	9.0	55		7.0	s/chl	4	0		3.0											B364672	257.56	259.08	**2.600**			VA05080698	1.52
3	1	1.5	3.5	50	70	20.0	chl/cb/q	5		0.1								5.0				B364673	259.08	260.60	**0.737**			VA05080698	1.52
2	1	1.0	2.0	50		2.0	q/chl	2	0		0.1											B364674	260.60	262.13	**0.187**			VA05080698	1.53
2	3	1.0	2.0	60		2.0	q/cb/chl	4	0		2.0																		
2	1	1.1	2.0	60		2.0	cb/q	5	0		3.0								5.0			B364675	262.13	263.65	**0.108**			VA05080698	1.52
																						B364676	BLANK		**<0.005**			VA05080698	
																						B364677	263.65	265.18	**0.227**			VA05080698	1.53
2	1	0.5	1.0	55		4.0	cb/q/s	4			10.0																		
1	3	8.0	8.0	40		60.0	cb/chl/s	5		5.0								5.0											
2	3	0.5	1.0	60		20.0	cb/s	4		0.1								5.0				B364678	265.18	266.70	**0.157**			VA05080698	1.52
4	1	1.0	4.0	50		4.0	q/chl	3	0		6.0											B364679	266.70	268.22	**0.201**			VA05080698	1.52
4	1	0.4	1.6	60	40	2.0	cb/q/s	4	0		3.0											B364680	268.22	269.75	**0.232**			VA05080698	1.53
3	1	0.5	1.3	60	80	1.0	q/chl	3			10.0											B364681	269.75	271.27	**0.164**			VA05080698	1.52
3	1	0.5	1.3	60	80	1.0	q/chl	3			10.0											B364682	269.75	271.27	**0.143**	DUP		VA05080698	1.52
5	1	2.0	6.5	50		4.0	q/cb/s	4	0		10.0		1.0									B364683	271.27	272.80	**0.736**		"clean" aspy	VA05080698	1.53
6	1	2.5	8.5	40	130	1.0	q/cb/s	4	0		10.0											B364684	272.80	274.32	**0.694**			VA05080698	1.52
5	1	6.0	8.0	50		0.5	q	4			6.0											B364685	274.32	275.84	**0.112**			VA05080698	1.52
5	1	2.0	6.0	30	60	3.0	q/chl	3		1.0	8.0						0.1					B364686	275.84	277.37	**1.145**		Moly	VA05080698	1.53
6	1	1.3	6.0	50	30	2.0	q/chl	4	0		14.0		0.1						4.0			B364687	277.37	278.89	**0.119**			VA05080698	1.52
3	1	1.0	2.0	50		1.0	q	3			2.0								4.0			B364688	278.89	280.42	**0.226**			VA05080698	1.53
1	3	1.2	1.2	60		3.0	q/s	3			2.0																		
3	1	1.0	2.0	50		1.0	q	3			2.0								4.0			B364689	278.89	280.42	**0.305**	PD/CA		VA05080698	1.53
1	3	1.2	1.2	60		3.0	q/s	3			2.0																		
																						B364690	STANDARD 5E		**1.445**	5E		VA05080698	
4	1	1.2	2.2	40	55	1.0	q/s	3			5.0											B364691	280.42	281.94	**0.303**			VA05080698	1.52
4	1	0.5	2.0	40		1.0	q/s	2			9.0								2.0			B364692	281.94	283.46	**0.232**			VA05080698	1.52
7	1	1.4	5.0	40	50	1.0	q/s	3			2.0									4.0		B364693	283.46	284.99	**0.378**			VA05080698	1.53
4	1	1.0	4.0	60		1.0	q/s	4	0		7.0											B364694	284.99	286.51	**0.051**			VA05080698	1.52
2	3	1.0	2.0	30		50.0	cb/s/chl	4																					
4	1	1.0	3.5	60		4.0	cb/s/chl	4			4.0											B364695	286.51	288.04	**0.517**			VA05080698	1.53
																						B364696	BLANK		**<0.005**			VA05080698	
7	1	1.0	5.0	60		2.0	q/chl	3	0		5.0											B364697	288.04	289.56	**0.282**			VA05080698	1.52
4	1	1.5	3.0	60	30	1.0	q/s	3	0		2.0											B364698	289.56	291.08	**0.384**			VA05080698	1.52
3	1	3.0	5.0	65		2.0	cb/s	4		1.0	4.0		2.0									B364699	291.08	292.61	**0.168**			VA05080698	1.53
1	1	3.0	3.0	60		8.0	cb/q/s	4											6.0										
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-304C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1179m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 5-10, 2005 | DATES LOGGING: Aug 28 - Sept 1, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 460054 NORTHING: 7099197

COORD SYSTEM: NAD 83: EASTING: 459935 NORTHING: 7099383

NAD 27 (CORRECTED for historic grid): EASTING: 460024 NORTHING: 7099207

SECTION LINE(historic grid)

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 5.79m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	5.79	Casing; No Recovery
5.79	309.36	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B364053 - B364180

Requisition #: MASP448STRGOL.05Q Date Shipped: 6-Sept-05

Lab Record #: VA05080930 Date Received: 20-Sept-05

Sample Sequence: B364181 - B364316

Requisition #: MASP448STRGOL.05Q Date Shipped: 9-Sept-05

Lab Record #: VA05080697 Date Received: 20-Sept-05

Duplicates:	364062; 364082; 364102; 364122; 364142; 364162; 364182; 365202; 365222; 365242; 365262; 365282; 365302
Preparation Duplicate/ Check Assay:	364069; 364089; 364109; 364129; 364149; 364169; 364189; 365209; 365229; 365249; 365269; 365289; 365309
Standards:	364070 (6F); 364090 (2B); 364110 (4D); 364130 (5E); 364150 (6F); 364170 (2B); 364190 (6F); 365210 (3C); 365230 (2B); 365250 (7G); 365270 (3C); 365290 (6F); 365310 (4D)
Blanks:	364056; 364076; 364096; 364116; 364136; 364136; 364156; 364176; 364196; 365216; 365236; 365256; 365276; 365296; 365316

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96		-51.7	In casing	
121.91	325.7	-52.1	351.7	352.7
182.87	326.8	-52.3	352.8	353.8
243.83	329.2	-52.5	355.2	356.2
309.36	327.5	-52.7	353.5	354.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

At 445 ft and 465 ft, 10 foot blocks instead of 5 foot blocks were placed, therefore the hole was 10 feet shorter than originally recorded.

Reduced from HQ to NQ at 398 ft (121.30m) due to bad ground

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE	of 12		
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 5.79m	0.00	5.79	Casing - No Recovery						
10	5.79 - 27.43	5.79	27.43	GND: Grey GND is extremely weathered, broken up, and oxidized; Crumbly; @ 12.9 - 13.4m. GND competent and much less oxidized.	5					
10		27.43	60.96	GND: GND is highly oxidized; Is broken-up into angular blocks with local clay alteration (up to 50cm) from 33.36 - 33.86m (clay alt'd core is also carb-rich); Fractured blocks all limonite stained and commonly with carbonate on faces; Blocks can appear to have been previously sericite/chlorite altered; Slickenlines: @60.46m face at 15° with lines at 85° TCA; Siderite common in veinlets/fractures and as subhedral crystals disseminated within sericite altered core.	5	1		1	1	
10		60.96	83.82	GND: GND is much more competent, but still moderately broken up (8cm avg pieces); GND is only moderately oxidized - mostly restricted to fractures and veinlets and altered selvages; @60.96 - 62.28m core appears highly oxidized and sericitized (pale rusty colour) and also clay and carbonate altered; @ 64.89 - 65.53m core is intensely clay + carb altered; Appears brecciated (floating quartz-eyes); Slickenlines: @65.22m face at 5°, lines at 30°; @ 68.69m face at 15° with lines at 30°; @81.70m face at 45°, lines at 60°.	3	1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	1	0.3	0.3	5														2.0				B364053	5.79	6.10	**0.375**			VA05080930	0.31
0																						B364054	6.10	7.62	**1.855**			VA05080930	1.52
0																						B364055	7.62	9.14	**0.660**			VA05080930	1.52
																						B364056	BLANK		**<0.005**			VA05080930	
0																						B364057	9.14	10.67	**0.468**			VA05080930	1.53
0																						B364058	10.67	12.19	**0.892**			VA05080930	1.52
0																						B364059	12.19	13.72	**0.056**			VA05080930	1.53
0																						B364060	13.72	15.24	**4.110**			VA05080930	1.52
0																						B364061	15.24	16.76	**0.552**			VA05080930	1.52
0																						B364062	15.24	16.76	**0.125**	DUP		VA05080930	1.52
0																						B364063	16.76	18.29	**0.112**			VA05080930	1.53
0																						B364064	18.29	19.81	**1.140**			VA05080930	1.52
2	1	20.0	25.0															4.0				B364065	19.81	21.34	**10.000**			VA05080930	1.53
																						B364066	21.34	22.86	**0.026**			VA05080930	1.52
																						B364067	22.86	24.38	**0.009**			VA05080930	1.52
																						B364068	24.38	25.91	**0.024**			VA05080930	1.53
																						B364069	24.38	25.91	**0.023**	PD/CA		VA05080930	1.53
																						B364070	STANDARD 3C		**0.089**	3C		VA05080930	
1	1	10.0	10.0																			B364071	25.91	27.43	**2.660**			VA05080930	1.52
1	1	3.0	3.0	20														2.0				B364072	27.43	28.96	**1.350**			VA05080930	1.53
1	1	1.0	1.0	60														2.0				B364073	28.96	30.48	**0.069**			VA05080930	1.52
0																						B364074	30.48	32.00	**0.432**			VA05080930	1.52
0																						B364075	32.00	33.53	**0.224**			VA05080930	1.53
																						B364076	BLANK		**<0.005**			VA05080930	
0																						B364077	33.53	35.05	**0.487**			VA05080930	1.52
0																						B364078	35.05	36.58	**0.097**			VA05080930	1.53
1	1	0.6	0.6	15		2.0		5	4									2.0				B364079	36.58	38.10	**0.435**			VA05080930	1.52
4	1	1.0	3.0	20		2.0	5	5	4									4.0				B364080	38.10	39.62	**0.404**			VA05080930	1.52
0																						B364081	39.62	41.15	**0.155**			VA05080930	1.53
0																						B364082	39.62	41.15	**0.068**	DUP		VA05080930	1.53
5	1	0.4	1.4	30														2.0				B364083	41.15	42.67	**0.149**			VA05080930	1.52
2	1	0.2	0.4	30														5.0				B364084	42.67	44.20	**0.424**			VA05080930	1.53
2	1	0.5	0.9	20														5.0				B364085	44.20	45.72	**0.838**			VA05080930	1.52
3	1	2.0	2.6	30														2.0				B364086	45.72	47.24	**1.105**			VA05080930	1.52
1	1	0.8	0.8	10														2.0				B364087	47.24	48.77	**1.195**			VA05080930	1.53
0																						B364088	48.77	50.29	**0.082**			VA05080930	1.52
0																						B364089	48.77	50.29	**0.082**	PD/CA		VA05080930	1.52
																						B364090	STANDARD 2B		**3.130**	2B		VA05080930	
0																						B364091	50.29	51.82	**0.050**			VA05080930	1.53
1	1	0.5	0.5	20														2.0				B364092	51.82	53.34	**0.140**			VA05080930	1.52
1	1	0.6	0.6	20														2.0				B364093	53.34	54.86	**0.090**			VA05080930	1.52
3	1	0.6	1.5	20														2.0				B364094	54.86	56.39	**0.087**			VA05080930	1.53
1	1	0.5	0.5	30														2.0				B364095	56.39	57.91	**0.419**			VA05080930	1.52
1	4	0.5	0.5	30														80.0											
																						B364096	BLANK		**<0.005**			VA05080930	
0																						B364097	57.91	59.44	**0.205**			VA05080930	1.53
0																						B364098	59.44	60.96	**0.059**			VA05080930	1.52
1	1	0.5	0.5	40														2.0				B364099	60.96	62.48	**0.240**			VA05080930	1.52
1	1	0.7	0.7	30														1.0				B364100	62.48	64.01	**0.094**			VA05080930	1.53
0																						B364101	64.01	64.89	**0.029**			VA05080930	0.88
0																						B364102	64.01	64.89	**0.052**	DUP		VA05080930	0.88

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 3 of 12	
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		83.82	89.92	GND: GND is highly fractured (full diameter of core is rare); Fractured faces are limonitic and react vigorously with HCl; Fracture faces with darker limonite staining only weakly react with HCl; Locally clay alteration is more intense at very shallow angles.	4			2		
10		89.92	92.96	GND: GND slightly less limonitic; GND moderately clay altered throughout with local intense clay alteration from 90.0 - 90.25m; Slight sericite alteration throughout (pale green color); Quartz veins vuggy from previous sulphides; Slickenlines: @92.36m face at 30°, lines at 45°.	2	2		3		
10		92.96	96.01	GND: Fairly competent and unaltered GND; Fracture faces with limonite and commonly with carb/calcite; Limonite selvages common with fractures.	1					
10		96.01	101.04	GND: GND is moderately limonitic; Core is highly broken, with rare full diameter core; Quartz veins are vuggy from previous sulphides.	1					
10		101.04	115.82	GND: Unaltered GND, very competent, grey in color; Limonite staining still present on fracture surfaces; Only very minor limonite selvages along fractures; Quartz veins are predominantly grey with distinct edges.						
10		115.82	127.75	GND: Grey GND which has been moderately oxidized; Core is moderately broken up (10cm avg); Fracture faces are limonitic, commonly with carbonate and calcite; Locally core is highly broken up (117.35 - 118.45m); Core reduces to NQ at 121.56m	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B364103	64.89	65.53	0.030			VA05080930	0.64
1	1	0.3	0.3	60														1.0				B364104	65.53	67.06	0.312			VA05080930	1.53
3	1	0.6	1.4	45	30													2.0				B364105	67.06	68.58	0.071			VA05080930	1.52
3	1	0.5	1.0	30														2.0				B364106	68.58	70.10	0.181			VA05080930	1.52
0																						B364107	70.10	71.63	0.048			VA05080930	1.53
3	1	1.0	1.4	40														2.0				B364108	71.63	73.15	0.208			VA05080930	1.52
3	1	1.0	1.4	40														2.0				B364109	71.63	73.15	0.233	PD/CA		VA05080930	1.52
																						B364110	STANDARD 4D		0.439	4D		VA05080930	
4	1	1.0	2.1	40	30						1.0											B364111	73.15	74.68	0.228		Po in one vein only	VA05080930	1.53
1	1	0.3	40.0															4.0				B364112	74.68	76.20	0.056			VA05080930	1.52
1	3	2.0	70.0															60.0											
1	1	1.5	1.5	30														2.0				B364113	76.20	77.72	0.185			VA05080930	1.52
5	1	2.0	5.0	40														2.0				B364114	77.72	79.25	0.084			VA05080930	1.53
3	1	1.2	16.0	30		0.5	q	5										2.0				B364115	79.25	80.77	0.141			VA05080930	1.52
																						B364116	BLANK		<0.005			VA05080930	
1	1	1.0	1.0	15						4.0	2.0							2.0				B364117	80.77	82.30	0.012			VA05080930	1.53
3	1	0.5	1.0	40																		B364118	82.30	83.82	<0.005			VA05080930	1.52
1	1	0.5	0.5	45														2.0				B364119	83.82	85.34	0.287			VA05080930	1.52
3	1	0.5	1.0	45														3.0				B364120	85.34	86.87	0.078			VA05080930	1.53
2	1	0.4	0.8	45														3.0				B364121	86.87	88.39	0.076			VA05080930	1.52
2	1	0.4	0.8	45														3.0				B364122	86.87	88.39	0.071	DUP		VA05080930	1.52
1	6	0.5	0.5	40														60.0				B364123	88.39	89.92	0.069			VA05080930	1.53
2	1	0.5	0.9	45														2.0				B364124	89.92	91.44	0.069			VA05080930	1.52
1	1	0.5	0.5	30														5.0				B364125	91.44	92.96	0.025			VA05080930	1.52
2	1	0.7	1.1	45						0.1	2.0		3.0					2.0				B364126	92.96	94.49	0.240			VA05080930	1.53
1	5	0.5	0.5	45									5.0																
1	1	1.5	1.5	40						1.0			10.0									B364127	94.49	96.01	0.148			VA05080930	1.52
1	1	0.5	0.5	45														2.0				B364128	96.01	97.54	0.035			VA05080930	1.53
1	1	0.5	0.5	45														2.0				B364129	96.01	97.54	0.042	PD/CA		VA05080930	1.53
																						B364130	STANDARD 5E		1.440	5E		VA05080930	
1	1	0.5	0.5	40														2.0				B364131	97.54	99.06	0.082			VA05080930	1.52
2	1	0.5	1.0	45														2.0				B364132	99.06	100.58	0.185			VA05080930	1.52
0																						B364133	100.58	101.04	0.231			VA05080930	0.46
4	1	1.0	2.5	40		0.5	q	3			5.0											B364134	101.04	102.26	0.157			VA05080930	1.22
5	1	1.0	3.5	45	20	1.5	q	2			4.0											B364135	102.26	103.63	0.120			VA05080930	1.37
1	4	0.5	0.5	45														1.0											
																						B364136	BLANK		<0.005			VA05080930	
9	1	1.4	5.5	45		1.0	q	3			3.0											B364137	103.63	105.16	0.721			VA05080930	1.53
7	1	0.5	3.0	45							2.0											B364138	105.16	106.68	0.235			VA05080930	1.52
10	1	1.2	5.6	40		1.0	q	2			2.0											B364139	106.68	108.20	0.120			VA05080930	1.52
7	1	1.0	5.0	40		1.0	q/chl	4			4.0											B364140	108.20	109.73	0.218			VA05080930	1.53
2	1	0.6	1.2	40							2.0											B364141	109.73	111.25	0.048			VA05080930	1.52
2	1	0.6	1.2	40							2.0											B364142	109.73	111.25	0.086	DUP		VA05080930	1.52
10	1	1.0	6.2	45																		B364143	111.25	112.78	0.197			VA05080930	1.53
4	1	1.0	2.3	45	30						7.0	0.1										B364144	112.78	114.30	0.165			VA05080930	1.52
2	1	1.2	1.5								5.0		2.0									B364145	114.30	115.82	0.235			VA05080930	1.52
1	6	0.2	0.2	30		2.0	q/s	4			50.0		10.0																
4	1	0.8	2.0	40		0.3	q/s	5		0.1	5.0		1.0					1.0				B364146	115.82	117.35	0.243			VA05080930	1.53
4	1	1.0	2.5	40														2.0				B364147	117.35	118.87	0.091			VA05080930	1.52
8	1	1.0	4.5	45							2.0							2.0				B364148	118.87	120.40	0.253			VA05080930	1.53
8	1	1.0	4.5	45							2.0							2.0				B364149	118.87	120.40	0.865	PD/CA		VA05080930	1.53
																						B364150	STANDARD 6F		2.760	6F		VA05080930	
2	1	0.7	1.0	45							2.0											B364151	120.40	121.92	0.109			VA05080930	1.52

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 5 of 12	
DRILL HOLE # : DG05-304C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		127.75	150.05	GND: GND appears unaltered and very competent; Fractures are limonitic with calcite/carbonate; Starting to see chlorite along fractures as well; @148.35 - 149.9m core is highly fractured (up to 4cm full diameter core), limonitic throughout with moderate clay alteration. Slickenlines: @150.25m face at 50° with lines at 150° TCA.						
10		150.05	176.77	GND: Very competent GND; GND is unaltered; no limonite visible; minor carbonate/calcite on fractures throughout; Carb/calcite fractures commonly have pale-green color due to chlorite +/- sericite; Rare fine grained biotite blebs (up to 4x4cm) observed in GND (no mineralization associated); Disseminated and locally smeared pyrite common on fracture faces; @ 172.23 - 172 m core is highly oxidized, crumbly and clay altered in contact with (30°) 12cm silicified and chloritized GND. Slickenlines: @ 159.5m face at 45° with lines at 45°; @ 164.35m face at 35° with lines at 35°; @ 175.32m face at 80° with lines at 80°; @ 175.46m face at 30° with lines at 70°; @ 179.3m face at 20° with lines at 20° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	0.8	1.6	40							2.0											B364152	121.92	123.44	0.198			VA05080930	1.52
5	1	0.5	1.6	40							2.0							1.0				B364153	123.44	124.96	0.067			VA05080930	1.52
1	3	0.5	0.5	40							2.0											B364154	124.96	126.49	0.025			VA05080930	1.53
1	1	0.4	0.4	40														2.0											
3	1	0.5	1.0	40	60	1.0	q	5			2.0		1.0					1.0				B364155	126.49	127.75	0.066			VA05080930	1.26
																						B364156	BLANK		<0.005			VA05080930	
5	1	1.0	2.2	40							2.0		1.0					1.0				B364157	127.75	129.54	0.046			VA05080930	1.79
7	1	1.0	4.0	40							3.0		0.1				0.1					B364158	129.54	131.07	0.075		Moly	VA05080930	1.53
3	1	0.6	1.5	40							2.0							1.0				B364159	131.07	132.59	0.736			VA05080930	1.52
7	1	0.6	4.2	40							4.0	0.1	0.1				0.1					B364160	132.59	134.11	0.281		Moly	VA05080930	1.52
3	1	0.3	0.7	40							2.0											B364161	134.11	135.64	0.041			VA05080930	1.53
3	1	0.3	0.7	40							2.0											B364162	134.11	135.64	0.033	DUP		VA05080930	1.53
2	1	1.0	1.2	40		0.5	q	5			2.0							1.0				B364163	135.64	137.16	0.039			VA05080930	1.52
3	1	1.0	1.6	40							2.0				0.1							B364164	137.16	138.68	0.171			VA05080930	1.52
3	1	1.0	1.9	40	60						1.0	0.1										B364165	138.68	140.20	0.039			VA05080930	1.52
1	5	1.0	1.0	40		0.3	q	5			2.0	0.1	0.1																
2	1	0.5	0.9	40	60						4.0	0.1										B364166	140.20	141.73	0.078			VA05080930	1.53
1	5	1.0	1.0	40							1.0																		
10	1	1.0	4.5	45	60	0.5	q	5			2.0	0.1	1.0									B364167	141.73	143.25	0.091			VA05080930	1.52
2	1	0.5	0.8	40							2.0		0.1									B364168	143.25	144.78	0.081			VA05080930	1.53
2	1	0.5	0.8	40							2.0		0.1									B364169	143.25	144.78	0.038	PD/CA		VA05080930	1.53
																						B364170	STANDARD 2B		2.910	2B		VA05080930	
0																						B364171	144.78	145.30	0.018			VA05080930	0.52
1	1	0.5	0.5	40														2.0				B364172	145.30	146.85	0.061			VA05080930	1.55
0																						B364173	146.85	147.83	0.066			VA05080930	0.98
8	1	0.8	4.0	40	60						2.0											B364174	147.83	148.93	0.077			VA05080930	1.10
3	1	1.0	2.0	40							1.0											B364175	148.93	150.05	0.229			VA05080930	1.12
																						B364176	BLANK		<0.005			VA05080930	
1	1	1.0	1.0	40							2.0											B364177	150.05	150.88	0.045			VA05080930	0.83
1	4	0.4	0.4	##																									
1	5	0.5	0.5	40							1.0																		
5	1	0.4	1.5	40							2.0	0.1					0.1					B364178	150.88	152.40	0.041		Moly	VA05080930	1.52
1	3	0.5	0.5	60							2.0																		
4	1	1.0	3.0	40							5.0	0.1	1.0				0.1					B364179	152.40	153.93	1.465			VA05080930	1.53
1	1	1.0	1.0	50									2.0									B364180	153.93	155.45	0.483			VA05080930	1.52
1	1	1.5	1.5	80							0.1	0.1										B364181	155.45	156.97	0.046			VA05080697	1.52
1	1	1.5	1.5	80							0.1	0.1										B364182	155.45	156.97	0.029	DUP		VA05080697	1.52
6	1	1.2	3.0	40		0.2	q	5			2.0		2.0									B364183	156.97	158.50	0.106			VA05080697	1.53
2	1	0.5	1.0	40	60						1.0											B364184	158.50	160.02	0.032			VA05080697	1.52
1	5	0.5	0.5	50						10.0	4.0		1.0																
3	1	0.8	1.4	40							2.0		1.0									B364185	160.02	161.55	0.105			VA05080697	1.53
6	1	1.2	3.0	40							2.0		1.0									B364186	161.55	163.07	0.135			VA05080697	1.52
3	1	0.5	1.2	30	40	0.3	q	5			1.0											B364187	163.07	164.60	0.196			VA05080697	1.53
6	1	1.8		45	35	0.2	q	5			3.0	0.1	1.0									B364188	164.60	166.12	0.152			VA05080697	1.52
6	1	1.8		45	35	0.2	q	5			3.0	0.1	1.0									B364189	164.60	166.12	0.148	PD/CA		VA05080697	1.52
																						B364190	STANDARD 6F		2.820	6F		VA05080697	
3	1	0.5	1.2	40							2.0		0.1									B364191	166.12	167.65	0.100			VA05080697	1.53
1	6	0.5	0.5	40							30.0	0.1	1.0																
1	1	0.8	0.8	35																		B364192	167.65	169.16	0.060			VA05080697	1.51
1	1	0.4	0.4	45														1.0				B364193	169.16	169.83	0.085			VA05080697	0.67
3	1	0.6	1.0	35	65						1.0	0.1										B364194	169.83	170.65	0.027			VA05080697	0.82
3	1	15.0	2.0	60	45						1.0											B364195	170.65	172.21	0.029			VA05080697	1.56

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 7 of 12	
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		176.77	179.80	GND: Grey GND, unaltered; Similar to previous interval (153.1 - 179.84m) but fractures are limonitic again +/- carb/calcite; Core moderately broken up (12cm avg).						
10		179.80	193.85	GND: GND is very broken up (3x3x11.5cm, avg); with unaltered GND (10cm, avg.); Broken core limonitic with carbonate on faces; Blocks of broken core are softer - clay alteration; @193.85m - 194.27m = Core is intensely clay altered and carbonate altered with slickenlines at contact (up hole), face is at 15° with lines at 30° TCA.	2			2		
10		193.85	197.38	GND: GND is very soft (clay/argillic alteration) with moderate carbonate alteration throughout; Core has a slight greenish hue; From 193.85 - 194.25m core is clay and appears brecciated (floating quartz clasts and soft GND clasts); @ 196.35 - 197.38m core is limonitic with evidence of massive pyrite vein (0.5cm). Slickenlines: @194.47m face is at 5° with lines at 40°, @195.00m face is at 65° with lines at 80° TCA.		1		5	3	
10		197.38	225.13	GND: GND similar to interval 179.8 - 193.85m but majority of broken blocks are not clay altered; @ 201.55m VG is observed with aspy within chloritic bleb between 2 adjacent grey quartz veins (0.4cm each) at 45° TCA - quartz veins have minor carb and chlorite throughout; One 1.4cm q/chl altered selvage observed along veins; Veins contain ~5% pyrrhotite and 2% aspy; Local sericite alteration from 211.66 - 212.48m with minor carbonate alteration; @ 214.98 - 215.07m intensive clay and carbonate alteration with sharp down hole contact at 40° with slickenlines at 70°; Slickenlines: @ 215.09m face at 5° and lines at 5°; @ 224.43m, face at 5° with lines at 40°.	2					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval					
						Selvages				Sulphides								Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B364196	BLANK		<0.005			VA05080697	
5	1	1.0	3.5	60	30						2.0						0.1					B364197	172.21	173.74	0.090		Moly	VA05080697	1.53
3	1	1.0	1.6	35	85						2.0						0.1					B364198	173.74	175.26	0.025		Moly	VA05080697	1.52
1	5	2.0	2.0	55						1.0																			
1	5	0.5	0.5	40		15.0	q/chl	5			1.0	0.1										B364199	175.26	176.77	0.028			VA05080697	1.51
2	1	1.0	1.5	45							1.0																		
4	1	1.0	2.2	40	50	2.0	q/chl	5			1.0											B364200	176.77	178.31	0.051			VA05080697	1.54
1	1	0.7	0.7	45																		**B365201**	178.31	179.80	0.049		**New Sample Book**	VA05080697	1.49
1	5	0.4	0.4	40		1.5	q/chl	4																					
1	3	0.3	0.3	40		0.5	q/chl	5			2.0	0.1																	
1	1	0.7	0.7	45																		B365202	178.31	179.80	0.045	DUP		VA05080697	1.49
1	5	0.4	0.4	40		1.5	q/chl	4																					
1	3	0.3	0.3	40		0.5	q/chl	5			2.0	0.1																	
0																						B365203	179.80	181.36	0.038			VA05080697	1.56
0																						B365204	181.36	182.88	0.598			VA05080697	1.52
1	1	0.3	0.3	40		0.3	q	s			2.0	0.1										B365205	182.88	184.40	0.034			VA05080697	1.52
3	1	0.4	1.2	40		0.3	q	4			2.0	0.1										B365206	184.40	185.92	0.095			VA05080697	1.52
1	1	0.2	0.2	45																		B365207	185.92	187.45	0.036			VA05080697	1.53
0																						B365208	187.45	188.98	0.026			VA05080697	1.53
0																						B365209	187.45	188.98	0.025	PD/CA		VA05080697	1.53
																						B365210	STANDARD 3C		0.093	3C		VA05080697	
1	1	0.4	0.4	35																		B365211	188.98	190.50	0.039			VA05080697	1.52
0																						B365212	190.50	192.15	0.013			VA05080697	1.65
0																						B365213	192.15	193.85	0.037			VA05080697	1.70
1	6	0.5	0.5	65						80.0												B365214	193.85	195.38	0.104			VA05080697	1.53
0																						B365215	195.38	197.38	0.176			VA05080697	2.00
																						B365216	BLANK		<0.005			VA05080697	
5	1	1.0	2.0	65	50	0.6	q/chl	5			3.0											B365217	197.38	198.90	0.420			VA05080697	1.52
1	5	0.5	0.5	50		0.5	q/chl	4			3.0																		
3	1	0.5	1.0	60		1.0	s/chl	4			1.0							5.0				B365218	198.90	199.64	0.128			VA05080697	0.74
2	5	0.8	1.2	60		0.2	q/chl	5			2.0		0.1																
9	1	1.0	6.0	60	80	1.0	q/chl	5			1.0							2.0				B365219	199.64	201.16	0.933			VA05080697	1.52
7	1	1.3	5.0	45		1.4	q/chl	4			2.0		1.0			0.1	0.1					B365220	201.16	202.69	0.084		Moly	VA05080697	1.53
2	1	0.5	1.8	45		1.0	q/chl	3			1.0											B365221	202.69	204.21	0.182			VA05080697	1.52
2	1	0.5	1.8	45		1.0	q/chl	3			1.0											B365222	202.69	204.21	0.161	DUP		VA05080697	1.52
3	1	1.5	4.5	60						2.0								2.0				B365223	204.21	205.74	0.069			VA05080697	1.53
1	3	1.2	30.0															5.0											
2	1	1.5	2.0	60														1.0				B365224	205.74	207.26	0.429			VA05080697	1.52
3	1	0.5	1.1	45	60	0.5	q/chl	3														B365225	207.26	208.79	0.018			VA05080697	1.53
1	1	0.5	0.5	30																		B365226	208.79	210.32	0.297			VA05080697	1.53
2	1	0.5	1.0	30	45						5.0											B365227	210.32	211.66	0.264			VA05080697	1.34
1	6	0.5	0.5	45									25.0																
1	1	0.3	0.3	45							1.0											B365228	211.66	212.48	0.040			VA05080697	0.82
1	1	0.3	0.3	45							1.0											B365229	211.66	212.48	0.045	PD/CA		VA05080697	0.82
																						B365230	STANDARD 2B		1.705	2B		VA05080697	
4	1	1.0	2.5	45		1.5	s	4			2.0											B365231	212.48	213.95	1.370			VA05080697	1.47
1	3	0.3	0.3	45							1.0																		
1	1	0.8	0.8	45						1.0												B365232	213.95	214.88	0.086			VA05080697	0.93
1	5	1.0	1.0	45																									
4	1	2.5	4.8	60	45						1.0											B365233	214.88	216.40	0.122			VA05080697	1.52

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 9 of 12		
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		225.13	225.74	GND: Core is extremely clay altered and sericite altered; Random clasts of calcite (0.5cm avg) throughout; Slickenlines at 225.37m with face at 45° and lines at 45° TCA; Sharp contact at both ends @ 35° TCA; Dark grey clay observed on fracture faces.		4		5	3	
10		225.74	228.00	GND: GND is highly fractured; Pieces of core average 2x2x2.5cm in size; Fracture faces are limonitic with white calcite on the surfaces; Rare pieces are very clay altered and limonitic throughout.	3					
10		228.00	246.23	GND: Grey GND is moderately broken up (5cm avg); Fracture faces have white calcite with sericite +/- chlorite alteration; GND has minor sericite alteration throughout; Clay alteration occurs locally from 234.7 - 234.85m with heavily fractured quartz veins. Slickenlines: @ 237.9m face at 40° and lines at 40°; @ 238.87m face at 30° with lines at 75°; @ 242.2m face at 5° with lines at 20°; @ 244.9m face at 30° with lines at 50°; @ 244.9m face at 5° with lines at 50°; @ 245.36m face at 20° with lines at 45° TCA.		2				
10		246.23	249.67	GND: GND is very sericite altered; Only quartz remains unaltered; Core is also moderately carbonate altered throughout; Locally core is extremely clay altered: from 246.55 - 246.75m (broken up qv with v f gr diss py), 248.38 - 248.54m, 249.56 - 249.67m; From 247.48 - 247.63m = 2 irregular sulphide veins (30° and 60° contact) ~3cm with black oxidized pyrite? and disseminated f gr euhedral pyrite; @ 247.19m = ~1cm q v is broken - irregular/displaced wi v f gr diss py; Between qv at 247.19m and sulphide veins at 247.48m is very sericitic core wi v f gr diss py blebs throughout (~12%); Slickenlines: @248.54m face at 30° with lines at 60° TCA.		4			3	
10		249.67	291.57	GND: GND similar as described from 228 - 246.23m but with intervals of intense ser + carb alteration; From 271.67 - 271.92m core is very silicified and slightly sericite altered; Rare pyrite and pyrrho vnlts found throughout ser alt'd core; Ser alt'd intervals @ 253.42 - 254.28m, 258.67 - 260.60m, 263.65 - 264.47m and 273.2 - 273.88m; Slickenlines: @ 253.2m 50°/80°, @ 255.3m 30°/75°, @257.4m 5°/45°, @262.12m 30°/60°, @266.0m 40°/40°, @278.15m 5°/70°, @285.44m 40°/45°, @290.5m 20°/50° TCA; Sericite alt'n from 286.07 - 286.38m.		2			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B365234	216.40	217.93	0.061			VA05080697	1.53
3	1	0.5	1.2	60							0.1											B365235	217.93	219.45	0.056			VA05080697	1.52
																						B365236	BLANK		<0.005			VA05080697	
2	1	0.6	1.2	40							1.0											B365237	219.45	220.98	0.100			VA05080697	1.53
2	1	0.5	0.5	45							0.1											B365238	220.98	222.50	0.154			VA05080697	1.52
2	1	0.5	0.9	30	40						1.0											B365239	222.50	224.03	0.964			VA05080697	1.53
1	1	0.8	0.8	60									0.1									B365240	224.03	225.13	1.620			VA05080697	1.10
0																						B365241	225.13	225.74	0.110			VA05080697	0.61
0																						B365242	225.13	225.74	0.037	DUP		VA05080697	0.61
0																						B365243	225.74	227.08	0.114			VA05080697	1.34
0																						B365244	227.08	228.00	0.187			VA05080697	0.92
0																						B365245	228.00	228.96	0.033			VA05080697	0.96
2	1	0.6	1.0	30	45						1.0											B365246	228.96	230.12	0.212			VA05080697	1.16
1	6	0.4	0.4	45		0.3	q/s	5			30.0																		
2	1	0.5	1.0	30	45						1.0											B365247	230.12	231.65	0.058			VA05080697	1.53
3	1	2.0	4.2	45		3.0	s/q	4		1.0												B365248	231.65	233.17	1.055			VA05080697	1.52
3	1	2.0	4.2	45		3.0	s/q	4		1.0												B365249	231.65	233.17	0.643	PD/CA		VA05080697	1.52
																						B365250	STANDARD 7G		4.710	7G		VA05080697	
1	1	0.3	0.3	30																		B365251	233.17	234.70	0.077			VA05080697	1.53
3	1	0.5	1.3	45	35	0.3	q	5			1.0											B365252	234.70	236.22	0.141			VA05080697	1.52
1	1	1.0	1.0	45		0.2	q	5														B365253	236.22	237.75	0.093			VA05080697	1.53
1	1	0.7	0.7	45							1.0											B365254	237.75	239.27	0.119			VA05080697	1.52
3	1	0.5	1.3	40	50	0.5	q	5			4.0	0.1										B365255	239.27	240.80	0.371			VA05080697	1.53
																						B365256	BLANK		<0.005			VA05080697	
1	5	0.5	0.5	50							2.0											B365257	240.80	242.32	0.064			VA05080697	1.52
1	1	0.5	0.5	60																									
1	1	0.5	0.5	60																		B365258	242.32	243.85	0.134			VA05080697	1.53
1	1	0.8	0.8	85																		B365259	243.85	245.36	0.033			VA05080697	1.51
1	1	1.0	1.0	85		0.4	s/q	5														B365260	245.36	246.23	0.032			VA05080697	0.87
0																						B365261	246.23	247.15	0.216			VA05080697	0.92
0																						B365262	246.23	247.15	0.549	DUP		VA05080697	0.92
3	6	3.0	7.0	45	30					50.0												B365263	247.15	247.63	6.330		Sulphides	VA05080697	0.48
2	1	0.5	0.7	45																		B365264	247.63	248.41	1.735			VA05080697	0.78
0																						B365265	248.41	249.67	0.091			VA05080697	1.26
0																						B365266	249.67	251.46	0.391			VA05080697	1.79
3	1	1.0	2.0	60							2.0											B365267	251.46	252.98	0.853			VA05080697	1.52
3	1	1.0	1.2	60							1.0											B365268	252.98	254.51	0.205			VA05080697	1.53
3	1	1.0	1.2	60							1.0											B365269	252.98	254.51	0.287	PD/CA		VA05080697	1.53
																						B365270	STANDARD 3C		0.093	3C		VA05080697	
2	1	2.0	3.0	80							2.0											B365271	254.51	256.03	0.630			VA05080697	1.52
1	1	2.0	2.0	85							0.1											B365272	256.03	257.56	0.236			VA05080697	1.53
2	1	0.8	1.6	45							2.0											B365273	257.56	259.09	1.265			VA05080697	1.53
2	1	0.4	0.7	60	85					1.0	1.0											B365274	259.09	260.60	0.778			VA05080697	1.51
2	1	0.5	1.0	80																		B365275	260.60	262.12	0.166			VA05080697	1.52
																						B365276	BLANK		<0.005			VA05080697	

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		291.57	300.23	GND has a greyish-green colour; Sericite alteration is prominent throughout except for various short (10cm) intervals of unaltered GND. K-spar is observed along quartz veins in selvages and as veinlets and euh-subhedral grains diss throughout ser alt'd core; Fractured faces commonly have black-dark green color (chl and biot); From 291.57 - 291.77m core is extremely clay and carb alt'd with brecciated quartz clasts/eyes; Interval 295.65 - 297.18m (B365305) wi qtz vn showing dextral displacement ~2cm at various angles; Slickenline: @192.07m face at 40° with lines at 50°; @294.0m 5°/5°; @295.75m 0°/45°.		4				3
		300.23	309.37	GND: Moderately fractured unaltered grey GND (8cm avg); Fracture faces contain white calcite with slight ser-+/- chl alteration; Local moderate clay alteration from 304.8 - 305.25m; 309.27 - 309.57m = fine grained "mafic" GND with weak ser alteration; Slickenlines: @303.7m face at 40° with lines at 45°; @ 205.35m = 5°/65°; @ 305.4m = 30°/50°; @ 306.7m = 5°/90°; @ 309.27m = 5°/85°.						
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	2.4	6.0	65	30	7.0	s/cb	5			4.0											B365277	262.12	263.65	0.595			VA05080697	1.53
3	1	1.2	2.2	65							2.0											B365278	263.65	265.18	0.050			VA05080697	1.53
1	3	0.8	0.8	60																										
1	1	0.5	0.5	65																		B365279	265.18	266.70	0.136			VA05080697	1.52
1	1	1.0	1.0	75							2.0											B365280	266.70	268.22	0.088			VA05080697	1.52
1	5	0.8	0.8	60																		B365281	268.22	269.75	0.064			VA05080697	1.53
1	5	0.8	0.8	60																		B365282	268.22	269.75	0.054	DUP		VA05080697	1.53
6	1	1.0	4.5	80	60						2.0											B365283	269.75	271.27	0.420			VA05080697	1.52
1	1	0.5	0.5	45							1.0											B365284	271.27	272.80	0.613			VA05080697	1.53
3	1	1.6	2.2	60							1.0											B365285	272.80	274.33	0.361			VA05080697	1.53
4	1	1.0	3.8	70	45	3.0	q/s	5			0.1											B365286	274.33	275.84	0.081			VA05080697	1.51
1	4	0.6	0.6	45																										
6	1	0.7	2.5	60							1.0											B365287	275.84	277.16	0.477			VA05080697	1.32
2	5	0.4	0.7	60		0.5	q	5			2.0											B365288	277.16	278.89	1.775			VA05080697	1.73
2	3	1.0	1.5	60		0.4	q	5			2.0																			
2	5	0.4	0.7	60		0.5	q	5			2.0											B365289	277.16	278.89	1.985	PD/CA		VA05080697	1.73
2	3	1.0	1.5	60		0.4	q	5			2.0																			
																						B365290	STANDARD 6F		2.870	6F		VA05080697	
8	1	1.0	4.5	60	45						1.0		0.1									B365291	278.89	280.42	0.305			VA05080697	1.53
1	1	0.5	0.5	60							1.0											B365292	280.42	281.94	0.940			VA05080697	1.52
1	5	1.0	1.0	60		2.0	q/chl	5			1.0																			
7	1	0.5	2.2			0.4	q/chl	5			2.0											B365293	281.94	283.46	0.396			VA05080697	1.52
1	3	0.5	0.5	0		1.0	q/s	5			1.0																			
5	1	0.8	2.7	60	0	0.3	q	5			1.0											B365294	283.46	284.99	0.103			VA05080697	1.53
3	1	0.7	1.4	45	15	0.5	q/s	4			1.0											B365295	284.99	286.52	0.199			VA05080697	1.53
																						B365296	BLANK		<0.005			VA05080697	
1	1	0.6	0.6	40																		B365297	286.52	288.04	0.199			VA05080697	1.52
1	3	0.4	0.4	40						2.0																				
1	1	0.6	0.6	30																		B365298	288.04	289.56	0.055			VA05080697	1.52
1	6	0.3	0.3	45							30.0																			
1	1	0.2	0.2	40							2.0											B365299	289.56	291.08	0.583			VA05080697	1.52
2	1	0.5	0.7	30							2.0											B365300	291.08	291.57	4.480			VA05080697	0.49
1	1	0.5	0.5	45						2.0												B365301	291.57	292.84	2.780			VA05080697	1.27
1	1	0.5	0.5	45						2.0												B365302	291.57	292.84	7.530	DUP		VA05080697	1.27
1	1	0.5	0.5	25						5.0												B365303	292.84	294.13	0.335			VA05080697	1.29
1	2	1.2	1.2	65		5.0	s/k	5														B365304	294.13	295.65	0.360			VA05080697	1.52
1	1	0.8	0.8	85						10.0																				
4	1	1.0	2.5	45	60						1.0											B365305	295.65	297.18	0.284			VA05080697	1.53
1	2	0.6	0.6	45																										
3	1	1.0	2.2	45	10	1.0	s/k	5		5.0	1.0											B365306	297.18	298.70	0.059		Py only in 1 vn	VA05080697	1.52
4	1	1.0	3.0	60						2.0												B365307	298.70	300.23	0.677			VA05080697	1.53
1	6	4.0	4.0	65						40.0																				
1	1	0.2	0.2	60							1.0											B365308	300.23	301.75	0.126			VA05080697	1.52
1	1	0.2	0.2	60							1.0											B365309	300.23	301.75	0.076	PD/CA		VA05080697	1.52
																						B365310	STANDARD 4D		0.466	4D		VA05080697	
2	1	0.3	0.6	45							1.0											B365311	301.75	303.28	0.055			VA05080697	1.53
4	1	1.5	2.8	45	10					1.0	2.0		0.1									B365312	303.28	304.80	0.457			VA05080697	1.52
0																						B365313	304.80	306.32	0.156			VA05080697	1.52
1	1	0.4	0.4	20							1.0											B365314	306.32	307.85	0.254			VA05080697	1.53
1	1	1.0	1.0	45																		B365315	307.85	309.37	0.484			VA05080697	1.52
																						B365316	BLANK		<0.005			VA05080697	

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-305C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1111m

BEARING: 180 | DIP: -55

DATES DRILLING: Aug 10-15, 2005 | DATES LOGGING: Aug 27 - Sept 1, 2005

LOGGED BY: Molodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459907 NORTHING: 7099589

COORD SYSTEM: NAD 83: EASTING: 459789 NORTHING: 7099774

NAD 27 (CORRECTED for historic grid): EASTING: 459877 NORTHING: 7099599

SECTION LINE(historic grid): 459875 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 1.52m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	1.52	Casing
1.52	99.27	MSED (HFLS)
99.27	102.11	GND
102.11	106.40	MSED (HFLS)
106.40	259.08	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B364700-B364740

Requisition #: MASP448STRGOL.05Q | Date Shipped: 9-Sept-05

Lab Record #: VA05080696 | Date Received: 20-Sept-05

Sample Sequence: B364741 - B364873

Requisition #: MASP448STRGOL.05Q | Date Shipped: 13-Sept-05

Lab Record #: VA05082980 | Date Received: 27-Sept-05

Duplicates:	364702; 364722; 364742; 364762; 364782; 364802; 364822; 364842; 364862
Preparation Duplicate/ Check Assay:	364709; 364729; 364749; 364769; 364789; 364809; 364829; 364849; 364869
Standards:	364710 (4D); 364730 (4D); 364750 (7G); 364770 (6F); 364790 (2B); 364810 (4D); 364830 (3C); 364850 (5E); 364870 (2B)
Blanks:	364716; 364736; 364756; 364776; 364796; 364816; 364836; 364856

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	151.3	-53.8	177.3	178.3
121.91	151.4	-55.3	177.4	178.4
182.87	150.3	-56.5	176.3	177.3
259.07	151.1	-57.0	177.1	178.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Tight hole at the top; Reamed casing down to 74 ft

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 1 of 10	
DRILL HOLE # : DG05-305C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	0-1.52	0.00	1.52	Casing						
81	1.52 - 9.14	1.52	9.14	HFLS: Deep purple and aphanitic. Banded with light brown-grey layers on a 1-2cm scale throughout section; minor rusty orange-brown on irregular fracture faces, also with late carbonate, sometimes incorporated as layers within this banded rock; Pale grey layers are silicified hard (cordierite), deep purple layers are scratchable with scriber; Foliations: @2.0m = 80-90°, @4.0m = 40°; @ 6.0m = 35°; @ 8.0m = 30°.	2	0	0	0	1	
80	9.14-23.78	9.14	23.78	MSED: Zone of brecciated MSED; No complete diameter core until 22.40 - 22.86m where oxidized MSED has a general foliation of 40°; Recovery btwn 5 and 42% except btwn 10.67-12.19m and from 22.86 - 23.78m where it improves, but is still crumbly, with oxidized, convoluted metabeds; Argillaceous alteration throughout section, related to sericitic replacement along metabeds; One sample taken from this section where one qtz vein cuts competent, complete core and pebbles are rich in pure quartz. Only trace oxidized pyrite present.	4	3	0	3	2	
81	23.78	23.78	28.56	Competent HFLS; Metabeds folded in places - open, rounded and box folds; Pale grey layers (mentioned from 1.52-9.14m) not present here; Quartz and quart/carb veins cut across foliation but contain no sulphides or gold.	1	1		1	1	
80	28.56-38.10	28.56	32.00	MSED: Sheared/brecciated MSED; Sample taken from 30.48-32.0m because oxidation and shear have made this section of variable composition ("mixed bag" of MSED's).	4	2		4	3	
80		32.00	38.10	MSED: Strong banding; Quartz veins incorporation into foliation.						
81	38.10-99.27	38.10	44.20	MSED: HFLS with 'globular' veins of pure quartz, incorporated into MSED foliation. Few crosscut (noted); Very deep purple to purplish grey here.	1	0	0	0	1	
81		44.20	47.92	MSED: Oxidized (light brown) zone, stemming into foliation from quartz veins; These veins have calcite int the centre very few sulphides; Still HFLS; From 44.15 - 46.8m is all oxidized, weakened MSED.	3	1		1	2	
81		47.92	57.41	MSED: HFLS with pure quartz incoroporated into foliation; This quartz may have once been veins; Few 'new' veins (crosscutting) have trace oxidized pyrite and occassionally aspy.					1	
81		57.41	60.48	MSED: Competent HFLS with incorporated quartz into foliation and few wide crosscutting quartz veins with noticeable selvages; Micaceous replacement of semthing (sulphides?) preset within some veins.		1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

PAGE 2 of 10

Selvage Alteration: phl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max. (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
0																							1.52	3.05					1.53
0																							3.05	4.57					1.52
0																							4.57	6.10					1.53
1	3	0.5	0.5	145						1.0	0.1		0.1										6.10	7.62					1.52
4	1	4.0	7.5	140		0.0				1.0			0.1									B364700	7.62	9.14	**0.053**			VA05080696	1.52
5	1	6.0	16.0	150		0.0				1.0							3.0					B364701	9.14	10.67	**0.139**		Chromite (???); Pieces of quartz, no sulphides	VA05080696	1.53
1	1	2.0	3.0																			B364702	9.14	10.67	**0.061**	DUP		VA05080696	1.53
2	1	2.0	3.0																				10.67	12.19					1.52
1	1	3.0	3.0																				12.19	13.72					1.53
1	1	1.0	1.0																				13.72	25.24					11.52
2	1	1.5	3.0	20																			25.24	16.76					-8.48
1	1	0.5	0.5																				16.76	18.29					1.53
0																							18.29	19.81					1.52
1	1	2.0	2.0																				19.81	21.34					1.53
4	1	3.0	8.0	140		0.0				0.1												B364703	21.34	22.86	**0.038**			VA05080696	1.52
0																							22.86	23.78				-	0.92
2	1	1.0	2.0	130		0.0				0.0													23.78	24.38			Parallel to foliation		0.60
4	1	3.0	5.0	135		1.0	q/cb	3	2								5.0					B364704	24.38	25.91	**0.059**		Moly at edges	VA05080696	1.53
2	1	8.0	10.0	130						0.1													25.91	27.43					1.52
5	1	1.0	5.0	130	20	0.5	q/cb	4	3	0.1							0.1	4.0				B364705	27.43	28.56	**0.255**			VA05080696	1.13
																							28.56	29.91					1.35
																							29.91	30.48					0.57
1	4	2.0	2.0							4.0								5.0				B364706	30.48	32.00	**0.090**			VA05080696	1.52
5	1	4.0	14.0	30		0.0				0.1								3.0				B364707	32.00	33.53	**0.011**		Trace Magenetite(?)	VA05080696	1.53
4	1	15.0	23.0	30	40																	B364708	33.53	35.05	**0.014**			VA05080696	1.52
4	1	15.0	23.0	30	40																	B364709	33.53	35.05	**0.023**	PD/CA		VA05080696	1.52
																						B364710	STANDARD 1A		**0.917**	1A		VA05080696	
9	1	5.0	14.0	30															3.0			B364711	35.05	36.58	**0.008**			VA05080696	1.53
6	4	24.0	70.0							4.0							0.1	5.0				B364712	36.58	38.10	**0.006**		Hematite Stain	VA05080696	1.52
1	1	1.0	1.0	10		0.0																	38.10	39.62					1.52
1	1	1.0	1.0	50		1.0	cb	2	1														39.62	41.15					1.53
1	1	0.6	0.6	50		2.0	q	1									0.1					B364713	41.15	42.67	**0.007**			VA05080696	1.52
1	4	0.3	0.3	30		1.0	q	4	2											8.0									
0																							42.67	44.20					1.53
3	1	1.0	2.0	40		1.0	q/cb	3	1														44.20	45.72					1.52
3	1	1.0	3.0	40		0.0				0.0													45.72	47.24					1.52
																							47.24	47.92					0.68
1	3	0.3	0.3	30		2.0	cb/q	1	1								0.1					B364714	47.92	48.77	**0.022**			VA05080696	0.85
2	1	1.0	2.0	40		1.0	q	1															48.77	50.29					1.52
4	1	1.0	4.0	50	60	2.0	q/s	3		1.0								5.0					50.29	51.82					1.53
1	1	2.0	2.0	20		1.0	cb	2		0.1								5.0					51.82	53.34					1.52
1	1	1.0	1.0	30		0.5	cb	2		0.1								5.0					53.34	54.86					1.52
0																							54.86	56.53					1.67
3	1	1.0	3.0	40		2.0	q/cb	3		1.0									5.0			B364715	56.53	57.41	**0.006**			VA05080696	0.88
																						B364716	BLANK		**<0.005**			VA05080696	
1	1	2.0	2.0	45		2.0	q/cb	3		0.0													57.41	57.91					0.50
4	1	3.0	5.5	40		2.0	cb/q	4	0	0.1								5.0					57.91	59.44					1.53
4	1	2.0	7.0	40	20	q	q/s	2		0.1								5.0		5.0		B364717	59.44	60.48	**0.010**			VA05080696	1.04

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 3 of 10	
DRILL HOLE # : **DG05-305C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chi, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81		60.48	64.61	MSED: Predominantly (75%) 'bleached', silicified HFLS; Color light brown to grey; Still aphanitic and finely layered.	1	2			1	
81		64.61	76.20	MSED: Deep purple HFLS to smokey beige color with large quartz veins - up to 80cm; Within these veins are patches of micaceous materials appearing to be retrograded from HFLS patches. Some have metallic sheen. Evidence of shear from 75.5 - 76.2 m, quartz veins moved sinistrally.		1	1		1	
81		76.20	80.77	MSED: Slightly more carbonate veinlets, so rock is broken up, rare full diameter, pieces <10cm.		1		1	2	
81		80.77	84.69	MSED: More oxidized, whole section limonite infused along metased layers; Crumbly and medium brown.	4	2	0	2	2	
81		84.69	88.39	MSED: HFLS competent except 30 cm with extra carbonate.		1		1	1	
81		88.39	97.54	MSED: Oxidized and sheared HFLS from 88.39 - 92.96m; Pale grey-light brown HFLS to end of section; From 96.01 - 97.54m shear and clay alteration.	2	2		2	1	
81		97.54	99.27	MSED: Sericitized pale light brown/grey HFLS; Very broken up.	1	3		1		
10	99.27 - 102.11	99.27	102.11	GND: Highly clay altered; Color is greenish beige to white; GND texture barely distinguishable as quartz-eyes, no foliation.		3	2	3	1	
81	102.11 - 106.40	102.11	106.40	MSED: HFLS metased again; Last meter of section shows GND texture overprinted by HFLS foliation; Quartz veins still squished into foliation with beige-grey HFLS; Quartz-carb veins (noted) are similar to those in the GND dyke above.	2	2		1	2	
10	106.40 - 259.08	106.40	120.30	GND: Very crumbly and weak, carb-infused.		1	1	2	4	
10		120.30	132.59	GND: Somewhat more competent GND: Regular fracturing at 60° and 135° TCA; Alternating between very crumbly and broken and competent over 1-2m intervals.		3	2	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

PAGE 4 of 10

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	4.0	4.0	55		0.0				2.0			0.1					5.0					60.48	60.96			Disseminated clean, euhedral aspy (3 grains seen).		0.48
3	1	3.0	9.0	50	70	0.0																	60.96	62.48					1.52
0																							62.48	64.01					1.53
2	1	4.0	6.0	70		2.0	q	3	0	1.0			1.0					5.0				B364718	64.01	64.61	**0.170**			VA05080696	0.60
1	1	80.0	80.0	60		0.0											0.1			8.0		B364719	64.61	65.53	**0.009**			VA05080696	0.92
2	1	25.0	32.0	60	110	1.0	q	3															65.53	66.80					1.27
4	1	30.0	33.0	50	140	1.0	q/cb	3												8.0			66.80	68.00					1.20
0																							68.00	68.58					0.58
4	1	2.0	4.5	30	60					0.1								5.0					68.58	70.10					1.52
1	1	1.0	1.0	50		1.0	s/q/cb	4	1	10.0								2.0				B364720	70.10	71.63	**0.017**		Shiny massive and euh py	VA05080696	1.53
2	4	0.3	0.6	24																									
3	1	20.0	24.0	45		10.0	q/s/cb	2	0	4.0								4.0					71.63	73.15					1.52
0																							73.15	74.68					1.53
1	1	2.0	2.0							0.1								5.0					74.68	76.20					1.52
0																							76.20	77.72					1.52
1	1	2.0	2.0																				77.72	79.25					1.53
0																							79.25	80.77					1.52
0																							80.77	82.30					1.53
2	1	2.0	4.0	25		0.0																	82.30	83.83					1.53
4	1	4.0	9.0	50		0.0																	83.83	85.34					1.51
2	1	1.0	2.0		0	q	4	0	0									5.0					85.34	86.87					1.53
4	1	3.0	7.0	40	50																		86.87	88.39					1.52
2	1	4.0	6.0	40		0.0				1.0								5.0					88.39	89.92					1.53
2	1	1.0	2.0	80	60	0.0				0.0													89.92	91.44					1.52
0																							91.44	92.96					1.52
1	1	2.0	2.0	60		0.0				5.0								3.0				B364721	92.96	94.15	**0.023**		Also diss py 1-2 cm from vein	VA05080696	1.19
1	3	1.0	1.0	50		1.0	cb	1		2.0								5.0											
1	1	2.0	2.0	60		0.0				5.0								3.0				B364722	92.96	94.15	**0.022**	DUP		VA05080696	1.19
1	3	1.0	1.0	50		1.0	cb	1		2.0								5.0											
0																							94.15	96.01					1.86
0																							96.01	97.54					1.53
3	1	1.0	3.0	50		0.0																	97.54	98.41					0.87
3	1	4.0	7.0	50	55	2.0	q/cb	4	0	4.0								5.0				B364723	98.41	99.27	**0.016**			VA05080696	0.86
3	1	0.5	1.5	10	55	0.0																B364724	99.27	100.58	**0.115**			VA05080696	1.31
2	3	0.5	1.0	50																		B364725	100.58	102.11	**0.075**			VA05080696	1.53
1	3	0.5	0.5	50						1.0								5.0				B364726	102.11	103.63	**0.054**			VA05080696	1.52
2	3	0.5	1.0	50						1.0												B364727	103.63	105.16	**0.013**			VA05080696	1.53
3	3	0.5	1.0	60		1.0	q	1														B364728	105.16	106.40	**0.051**			VA05080696	1.24
3	3	0.5	1.0	60		1.0	q	1														B364729	105.16	106.40	**0.042**	PD/CA		VA05080696	1.24
																						B364730	STANDARD 4D		**0.447**	4D		VA05080696	
3	1	1.0	2.0	61		0.0																B364731	106.40	107.54	**0.072**			VA05080696	1.14
2	1	1.0	2.0	70		20.0	q/s/cb	4		5.0								5.0				B364732	107.54	108.20	**0.084**			VA05080696	0.66
3	1	1.0	3.0	70						5.0								5.0				B364733	108.20	109.73	**0.065**			VA05080696	1.53
1	3	0.3	0.3	60		2.0	cb/s	4		1.0								5.0											
4	1	1.5	3.0	80		6.0	q/s/cb	4		4.0								5.0				B364734	109.73	111.25	**0.113**			VA05080696	1.52
1	6	0.5	0.5	40						100.0								5.0				B364735	111.25	112.78	**0.040**			VA05080696	1.53
																						B364736	BLANK		**<0.005**			VA05080696	
4	1	1.0	3.0	80						0.1								5.0				B364737	112.78	114.30	**0.203**			VA05080696	1.52
2	1	2.5	5.0	50							5.0											B364738	114.30	115.82	**0.171**		po-bt	VA05080696	1.52
1	1	1.5	1.5	50		1.0	q/s	3	0		3.0											B364739	115.82	116.33	**0.054**			VA05080696	0.51
3	1	1.0	2.0	80		2.0	cb/chl/s	4	0		3.0											B364740	116.33	117.35	**0.029**			VA05080696	1.02
3	1	1.0	3.0	60		2.0	q/cb	1			2.0											B364741	117.35	118.87	**0.090**			VA05082980	1.52
3	1	1.0	3.0	60		2.0	q/cb	1			2.0											B364742	117.35	118.87	**0.097**	DUP		VA05082980	1.52
1	6	0.3	0.3	60		2.0	cb/s/q	4		96.0			4.0					5.0				B364743	118.87	120.30	**0.201**		Flattened aspy	VA05082980	1.43
2	1	1.0	1.6	50		12.0	q/cb/s	5														B364744	120.30	121.50	**0.666**			VA05082980	1.20

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 5 of 10	
DRILL HOLE # : **DG05-305C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		132.59	146.30	GND: Somewhat broken up by crumbly carbonate infusion.		2	1	1	3	
10		146.30	153.92	GND: @147.25 - 147.83m, two 2cm quartz veins contain massive po; One vein contains more po than quartz; These are the only sulphide bearing zones in the 1.53m sample; Po-bearing quartz veins 1cm or less, continue through unaltered, competent GND.		1			1	
10		153.92	163.07	GND: Moderately infused with carbonate GND.	0	1	0	1	2	
10		163.07	167.64	GND continues but with much larger veins (up to 20cm), plus small ones ~1cm; Pyrrhotite is euhedral, in grains 2-3mm in diameter, and massive, in aggregates up to 2cm, often the full width of the vein. Magnetic.						
10		167.64	188.98	GND: Still unaltered GND; Quartz veins sheeted, smaller and with less mineralization of sulphides (4% po at most); Sulphides decrease to a minimum of 0-2% between 181 and 188m; Last interval has 2 veins with aspy, disseminated tiny grains (≤ 1mm) through vein and selvage. Half altered to scorodite.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	6.0	6.0	80						1.0								5.0				B364745	121.50	122.86	**0.389**		broken core	VA05082980	1.36
3	1	1.0	2.0	70	45	0.0				2.0	10.0									3.0		B364746	122.86	123.44	**0.019**			VA05082980	0.58
5	1	0.5	2.5	70	35						4.0									4.0		B364747	123.44	124.97	**0.018**			VA05082980	1.53
3	1	1.0	3.0	50		0.0					3.0		0.1							3.0		B364748	124.97	126.49	**0.064**			VA05082980	1.52
1	6	0.6	0.6	60		8.0	cb/q	5	0	100.0								5.0										
3	1	1.0	3.0	50		0.0					3.0		0.1							3.0		B364749	124.97	126.49	**0.060**	PD/CA		VA05082980	1.52
1	6	0.6	0.6	60		8.0	cb/q	5	0	100.0								5.0										
																						B364750	STANDARD 7G		**4.540**	7G		VA05082980	
4	1	1.5	4.6	40	80	1.0	q/s	3	0		5.0									2.0		B364751	126.49	128.02	**0.076**			VA05082980	1.53
3	1	12.0	23.0	50	70	30.0	cb/s/chl	4	0				9.0									B364752	128.02	129.54	**1.465**		Massive aspy at vn boundary	VA05082980	1.52
5	1	4.0	7.0	40		10.0	cb/s/chl	4			4.0		2.0									B364753	129.54	131.06	**0.088**			VA05082980	1.52
2	1	1.0	2.0	50		1.0	q/s	2			2.0											B364754	131.06	132.59	**0.137**			VA05082980	1.53
1	4	0.3	0.3	50		6.0	cb/s/chl	4		4.0								5.0	5.0									
5	1	3.0	7.5	55		1.0	q/cb	3			10.0	0.1			2.0							B364755	132.59	134.11	**0.066**			VA05082980	1.52
																						B364756	BLANK		**<0.005**			VA05082980	
6	1	3.0	6.0	50	20	1.0	cb/s	2			2.0									4.0		B364757	134.11	135.64	**0.171**			VA05082980	1.53
1	3	1.5	1.5	60		10.0	q	1																				
1	1	1.0	1.0	50		0.5	q	3			4.0								2.0	2.0		B364758	135.64	137.16	**0.058**			VA05082980	1.52
2	3	1.5	2.0	40		3.0	q/cb	4			15.0								5.0	2.0								
5	1	1.0	5.0	60		1.0	q	2			3.0									3.0		B364759	137.16	138.68	**0.042**			VA05082980	1.52
1	1	1.5	1.5	50		0.0					5.0											B364760	138.68	140.21	**0.065**			VA05082980	1.53
4	1	1.0	4.0	40		2.0	cb/s	4	0		6.0									1.0		B364761	140.21	141.73	**0.088**			VA05082980	1.52
4	1	1.0	4.0	40		2.0	cb/s	4	0		6.0									1.0		B364762	140.21	141.73	**0.393**	DUP		VA05082980	1.52
3	1	1.0	2.0	40		1.0	q	4			7.0									3.0		B364763	141.73	143.26	**0.100**			VA05082980	1.53
2	1	1.0	2.0	40	30	1.0	q	4			10.0											B364764	143.26	144.78	**0.050**			VA05082980	1.52
2	1	1.5	3.0	30		1.0	q	4			5.0											B364765	144.78	146.30	**0.046**			VA05082980	1.52
2	6	2.0	4.0	60		4.0	q/cb/s	2			55.0											B364766	146.30	147.83	**0.235**			VA05082980	1.53
2	1	2.0	3.0	70		1.0																B364767	147.83	149.35	**0.050**			VA05082980	1.52
2	1	2.0	3.0	60		1.0	q/s	3	1		6.0									1.0		B364768	149.35	150.88	**2.060**			VA05082980	1.53
2	1	2.0	3.0	60		1.0	q/s	3	1		6.0									1.0		B364769	149.35	150.88	**0.072**	PD/CA		VA05082980	1.53
																						B364770	STANDARD 6F		**2.840**	6F		VA05082980	
4	1	1.0	2.0	60	20	1.0	q	3	0		5.0											B364771	150.88	152.40	**0.076**			VA05082980	1.52
4	1	1.0	3.0	25	50	1.0	q/cb/s	3	0		2.0		1.0									B364772	152.40	153.92	**0.803**			VA05082980	1.52
1	4	1.0	1.0	20		0.0				0.0												B364773	153.92	155.45	**0.125**			VA05082980	1.53
1	1	0.5	0.5	40		1.0	q/s	4														B364774	155.45	156.97	**0.021**			VA05082980	1.52
0																						B364775	156.97	158.50	**<0.005**			VA05082980	1.53
																						B364776	BLANK		**<0.005**			VA05082980	
1	1	1.0	1.0	50							3.0								4.0	1.0		B364777	158.50	160.02	**0.026**			VA05082980	1.52
1	1	2.0	2.0	50		2.0	q	4														B364778	160.02	161.54	**0.032**			VA05082980	1.52
2	1	1.0	2.0	40		2.0	q	4	0		10.0				1.0					1.0		B364779	161.54	163.07	**0.017**			VA05082980	1.53
3	1	20.0	22.5	25		15.0	cb/s/chl	5	0		3.0											B364780	163.07	164.59	**0.245**			VA05082980	1.52
3	1	14.0	24.0	35		10.0	cb/s/chl	5		1.0	8.0	3.0	0.1									B364781	164.59	165.18	**0.204**			VA05082980	0.59
3	1	14.0	24.0	35		10.0	cb/s/chl	5		1.0	8.0	3.0	0.1									B364782	164.59	165.18	**0.164**	DUP		VA05082980	0.59
1	4	2.0	6.0	25	15	1.0	q/cb	3				12.0	0.1									B364783	165.18	166.12	**0.313**			VA05082980	0.94
4	1	3.0	6.0	30		1.0	q/cb	2			2.0											B364784	166.12	167.64	**0.049**			VA05082980	1.52
4	1	1.0	3.5	40		10.0	cb/s/q/chl	5	0		3.0	0.1	7.0		1.0							B364785	167.64	169.03	**0.239**			VA05082980	1.39
4	1	1.0	3.2	40	50	2.0	q	2	0		1.0											B364786	169.03	170.69	**0.049**			VA05082980	1.66
3	4	0.3	1.1	70		20.0	cb/s	5	0																			
2	1	3.0	4.0	40		2.0	q/cb	5	0		2.0									2.0		B364787	170.69	172.21	**0.235**			VA05082980	1.52
5	1	4.0	7.0	40	25	1.0	q	3			2.0	0.1								2.0		B364788	172.21	173.74	**0.219**			VA05082980	1.53
5	1	4.0	7.0	40	25	1.0	q	3			2.0	0.1								2.0		B364789	172.21	173.74	**1.120**	PD/CA		VA05082980	1.53
																						B364790	STANDARD 2B		**2.970**	2B		VA05082980	
6	1	2.0	7.0	30	45																	B364791	173.74	175.26	**0.172**			VA05082980	1.52
4	1	1.2	3.6	50	25	1.0	q/cb	3			2.0											B364792	175.26	176.78	**0.075**			VA05082980	1.52
4	1	1.5	2.6	50	30	6.0	1/cb/s	4		1.0	4.0								1.0	1.0		B364793	176.78	178.31	**0.035**			VA05082980	1.53
4	1	1.0	3.5	30		1.0	q/cb	2			4.0									1.0		B364794	178.31	179.83	**0.067**			VA05082980	1.52
3	1	3.0	5.0	50		2.0	q/cb	1			1.0		10.0					2.0				B364795	179.83	181.36	**1.495**		Aspy conc at edges of one 3 cm vn.	VA05082980	1.53

DRILL LOG LEGEND - P1	DATE: August 27 - Sept 1, 2005	PAGE 1 of 10	
DRILL HOLE # : **DG05-305C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		188.98	205.21	GND: @ 190.5, 8cm of pure quartz (vein) is presenrved, but pebbles and lack of upper contact indicate some loss of recovery; From 190.9 to 193.3m is fault material; 40cm of brecciated quartz and GND within brown gouge material, followed by moderately re-arranged quartz veins (no selvage as all moved) black clay seams (veinlets) and slight brecciation all infused with carbonate. Two large quartz veins (18cm and 24cm) in the section, thickness unknown, assumed contacts @~50° TCA; Outside of this zone, the section is unaltered GND with sulphide-rich veins, occassional trace VG; Except from 201.07 - 201.78m, evidence of shear and limonite infusion, where rock is moderately broken up with limonite on faces.	1	2	1	1	2	
10		205.21	217.93	GND: Mostly (60%) moderately altered GND; Zones of carbonate (208.5 - 208.7m and 208.0 - 208.3m); Zone of limonite (209.5 - 210.8m); Zone of sericite (211.0 - 213.0m); Rest of unaltered GND with few quartz veins, not much mineralization.	2	2	1	0	2	
10		217.93	226.62	GND: Unaltered GND with quartz veins; Good mineralization but a lot of alteration within veins, po to bt and other minerals to chlorite; These are positioned within veins where sulphides are normally found.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, qp = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B364796	BLANK		<0.005			VA05082980	
2	1	1.0	2.0	30	0	1.0	q	2			0.1											B364797	181.36	182.88	0.043			VA05082980	1.52
3	1	1.2	3.0	40		1.0	q/s	2			2.0									4.0		B364798	182.88	184.40	0.036			VA05082980	1.52
2	1	0.8	1.3	50		0.5	q	4			2.0				1.0							B364799	184.40	185.93	0.185		VG?	VA05082980	1.53
2	1	1.0	2.0	30		2.0	q/s/cb	3			1.0									2.0		B364800	185.93	187.45	0.019			VA05082980	1.52
3	1	1.0	3.0	35	15	4.0	cb/s	5			1.0		2.0				0.1		2.0			B364801	187.45	188.98	0.200		Trace VG?	VA05082980	1.53
3	1	1.0	3.0	35	15	4.0	cb/s	5			1.0		2.0				0.1		2.0			B364802	187.45	188.98	0.338	DUP	Trace VG?	VA05082980	1.53
3	3	1	6.0	8.0	20	0	0.2	cb/s	3		2.0	8.0	2.0				0.1					B364803	188.98	189.73	1.320		Trace VG?	VA05082980	0.75
3	1	1.5	2.1	15	50	2.0	q/cb	3		3.0								5.0				B364804	189.73	190.50	2.500			VA05082980	0.77
4	1	8.0	11.0	60	30	2.0	q/s	4		4.0								3.0				B364805	190.50	192.02	2.190		Poor recovery	VA05082980	1.52
1	1	18.0	18.0	50		8.0	cb/s	3		5.0	2.0							5.0				B364806	192.02	192.37	5.890			VA05082980	0.35
3	1	3.0	6.5	50	20	0.0				10.0								2.0				B364807	192.37	192.85	2.590			VA05082980	0.48
2	1	24.0	30.0	40		4.0	s/q	3		7.0							1.0	3.0				B364808	192.85	193.69	19.300		moly	VA05082980	0.84
2	1	24.0	30.0	40		4.0	s/q	3		7.0							1.0	3.0				B364809	192.85	193.69	13.050	PD/CA		VA05082980	0.84
																						B364810	STANDARD 4D		0.427	4D		VA05082980	
1	1	6.0	6.0	20		8.0	q/cb/s	3		10.0	1.0	5.0										B364811	193.69	194.30	3.190		One veins continues into next sample	VA05082980	0.61
3	1	6.0	10.0	20	30	6.0	q/cb/s	3		5.0	3.0	4.0	2.0			0.1						B364812	194.30	195.07	8.960		Vein continues to this sample	VA05082980	0.77
2	1	15.0	16.0	20		10.0	q/cb/s	4			2.0	0.1										B364813	195.07	195.73	0.164			VA05082980	0.66
2	1	1.0	1.5	25	70	1.0	cb/q	4	0		3.0		0.1							10.0		B364814	195.73	196.60	0.172			VA05082980	0.87
2	1	1.5	2.5	25		3.0	q/s	4			1.0						0.1					B364815	196.60	198.12	0.134			VA05082980	1.52
																						B364816	BLANK		<0.005			VA05082980	
1	1	1.0	1.0	30		2.0	q/s	3			2.0		1.0						2.0			B364817	198.12	199.64	0.124			VA05082980	1.52
6	1	1.5	3.8	25	0	2.0	cb/q/s	4	0		6.0	0.1	0.1						2.0	5.0		B364818	199.64	201.07	0.308			VA05082980	1.43
1	1	2.0	2.0	10		2.0	q/s	2		2.0								5.0				B364819	201.07	201.78	0.307			VA05082980	0.71
1	4	0.3	0.3	40		8.0	cb/s	5														B364820	201.78	202.69	0.024			VA05082980	0.91
1	1	1.0	1.0	20		6.0	q/cb/s	4			3.0								3.0			B364821	202.69	204.22	0.189			VA05082980	1.53
1	3	1.0	1.0	35		4.0	q/cb/s	4																					
1	1	1.0	1.0	20		6.0	q/cb/s	4			3.0								3.0			B364822	202.69	204.22	0.071	DUP		VA05082980	1.53
1	3	1.0	1.0	35		4.0	q/cb/s	4																					
2	3	0.5	1.0	30	40	2.0	cb/chl	4			1.0		0.1						3.0			B364823	204.22	205.21	0.208			VA05082980	0.99
1	1	1.0	1.0	20		1.0	q/s/chl	3			10.0																		
4	1	10.0	13.0	25	15	10.0	s/cb/chl	5	3	4.0	2.0		1.0		1.0							B364824	205.21	205.74	0.553			VA05082980	0.53
3	1	2.0	4.0	30		10.0	cb/s	3	4	2.0								5.0				B364825	205.74	206.51	0.367			VA05082980	0.77
3	1	1.0	3.0	15							2.0		2.0						1.0	5.0		B364826	206.51	207.26	0.182			VA05082980	0.75
2	1	2.0	2.0	25		4.0	q/s	5		1.0					0.1			5.0				B364827	207.26	208.79	0.139			VA05082980	1.53
2	3	1.0	2.0	25		10.0	cb/s	3		2.0			0.1					5.0											
2	1	1.0	2.0	40	10	1.0	q	3		2.0	2.0							5.0		1.0		B364828	208.79	210.31	0.172			VA05082980	1.52
2	1	1.0	2.0	40	10	1.0	q	3		2.0	2.0							5.0		1.0		B364829	208.79	210.31	0.235	PD/CA		VA05082980	1.52
																						B364830	STANDARD 3C		0.090	3C		VA05082980	
2	3	1.0	3.0	20		4.0	q/s	3		5.0	3.0		0.1					5.0	2.0	3.0		B364831	210.31	211.84	0.943			VA05082980	1.53
1	6	0.3	0.3	10		10.0	cb/chl	3		100.0								5.0				B364832	211.84	213.26	0.111			VA05082980	1.42
3	1	1.0	3.0	20		1.0	q/s	2		3.0	3.0							3.0											
4	1	1.0	4.0	40	25	8.0	q/s	4	0		1.0									3.0		B364833	213.26	214.88	0.245			VA05082980	1.62
6	1	2.0	5.0	30	20	2.0	q/cb/s	4		5.0	3.0				1.0				2.0			B364834	214.88	216.41	0.368			VA05082980	1.53
5	1	2.0	5.0	35	25	4.0	q/cb/s	3	0	1.0	3.0	0.1										B364835	216.41	217.93	0.093			VA05082980	1.52
																						B364836	BLANK		<0.005			VA05082980	
1	1	4.0	4.0	20		10.0	cb/s	5	0													B364837	217.93	219.46	0.077			VA05082980	1.53
2	1	1.5	2.5	20		1.0	q	4	0		1.0		0.1						3.0	3.0		B364838	219.46	220.98	0.049			VA05082980	1.52
1	1	2.0	2.0	40		5.0	q/s	3	0	1.0	0.1							5.0				B364839	220.98	222.50	0.038			VA05082980	1.52
1	3	1.0	1.0	30		3.0	q/cb	4	0		5.0																		
2	1	0.5	1.0	20		1.0	q	3			2.0									3.0		B364840	222.50	224.03	0.126			VA05082980	1.53
4	1	1.0	3.3	60	15	1.0	q/s	4	0		2.0									3.0		B364841	224.03	225.55	0.093			VA05082980	1.52
4	1	1.0	3.3	60	15	1.0	q/s	4	0		2.0									3.0		B364842	224.03	225.55	0.063	DUP		VA05082980	1.52

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 9 of 10	
DRILL HOLE # : DG05-305C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		226.62	244.14	GND: Moderately sheared GND: Most quartz veins are only partially present (some are moved/sheared) usually into ~30° TCA angle; Infusion of clay minerals and carbonate weaken rock; Between 237.74 - 239.27m, three quartz veins appear; 2 dark grey quartz veins at 5° TCA with carbonitic selvages (competent), as well as one milky quartz vein within the usual quartz/sericite selvage; @ 241.35m a 4cm concentration of fresh mafic minerals appears, generally at 40° TCA, includes bt, cpx, hb, ser; Last sample, 243.28 - 244.14m, is 75% rearranged, sheared; Quartz eyes within grey clay, trending with fine laminations at 70° TCA; Matrix of GND infused with sericite and carbonate; Clear boundary with next section, at 130° TCA.	1	3	1	2	3	
10		244.14	259.08	GND: Highly altered GND; One large quartz vein with 3 other large quartz veins in one 1m sample (251.46 - 252.00m) contains oxidized and unoxidized pyrite; Alteration pervasive across entire section, with yellowish green color, predominantly calcite and sericite; First three meters are black silicified GND with 2-10cm 'selvages' around microfractures - no vein, only selvage. Pale beige-green in color; All competent core except directly adjacent to largest quartz vein, where carbonitic clay infuses sericite-rich selvage to form gouge-clay for 10cm on either boundary.	1	4	1	1	3	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	20.0	23.5	40	25	4.0	q/s	3		4.0	8.0							1.0				B364843	225.55	226.62	**5.760**			VA05082980	1.07
							cb	1																					
1	1	1.0	1.0	40		0.0					0.1									6.0		B364844	226.62	228.14	**0.824**			VA05082980	1.52
3	1	4.0	8.5	40	50	2.0	q/cb	5	0	1.0	5.0	2.0						5.0				B364845	228.14	229.14	**0.928**			VA05082980	1.00
1	1		1.0	25		2.0	q/cb	2			0.1								2.0			B364846	229.14	230.12	**0.124**			VA05082980	0.98
3	1	1.0	2.5	25	60	3.0	q/cb	3		2.0	1.0							1.0		2.0		B364847	230.12	231.65	**0.861**			VA05082980	1.53
1	3	0.5	0.5	130		2.0	q/cb/s	4																					
5	1	1.0	3.6	30		2.0	q/s/cb	4			3.0											B364848	231.65	233.17	**0.189**			VA05082980	1.52
5	1	1.0	3.6	30		2.0	q/s/cb	4			3.0											B364849	231.65	233.17	**0.459**	PD/CA		VA05082980	1.52
																						B364850	STANDARD 5E		**1.505**	5E		VA05082980	
4	1	1.0	4.0	40	5	4.0	q/s	4		2.0	2.0							5.0				B364851	233.17	234.70	**0.459**			VA05082980	1.53
1	1	0.4	0.4	30		4.0	q/s	4			5.0									2.0		B364852	234.70	236.22	**0.287**			VA05082980	1.52
3	4	0.2	0.6	90	5	10.0	cb/s	5																					
2	1	1.0	2.0	20		2.0	q/cb	4			1.0											B364853	236.22	237.74	**0.121**		Grey quartz	VA05082980	1.52
3	1	1.5	35.0	5	20	6.0	q/cb	5		2.0	10.0	0.1										B364854	237.74	239.27	**0.421**		Dark grey quartz	VA05082980	1.53
						4.0	cb/s	4			3.0																Milky quartz		
3	1	0.5	1.5	15	30	4.0	cb/s	4		1.0	0.1						0.1					B364855	239.27	240.79	**1.310**		Moly	VA05082980	1.52
																						B364856	BLANK		**<0.005**			VA05082980	
4	1	1.0	4.0	20		2.0	cb/s	4		1.0	1.0							5.0		4.0		B364857	240.79	242.32	**0.521**			VA05082980	1.53
	1	1.0	2.0	40		1.0	q	3			0.1								2.0			B364858	242.32	243.28	**0.043**			VA05082980	0.96
																						B364859	243.28	244.14	**0.144**			VA05082980	0.86
0																													
1	1	1.0	1.0	20		1.0	q/s	2		0.1	3.0							5.0				B364860	244.14	245.36	**0.418**			VA05082980	1.22
1	4	0.4	0.4	80		0.0				0.1								5.0											
4	1	1.0	4.0	25		6.0	s/chl/cb	5			8.0		2.0									B364861	245.36	246.89	**0.530**			VA05082980	1.53
4	1	1.0	4.0	25		6.0	s/chl/cb	5			8.0		2.0									B364862	245.36	246.89	**0.186**	DUP		VA05082980	1.53
5	1	0.3	1.5	20	45	0.0				2.0	10.0		2.0					5.0				B364863	246.89	248.41	**0.246**			VA05082980	1.52
2	1	1.5	3.0	60	25	4.0	q/cb/s	5		5.0								3.0				B364864	248.41	249.94	**0.371**			VA05082980	1.53
6	1	0.5	3.0	40	20	1.0	q/cb/s	5		1.0	2.0							5.0				B364865	249.94	251.46	**0.143**			VA05082980	1.52
4	1	25.0	34.0	70	25	10.0	cb/s	5	1	5.0								2.0				B364866	251.46	252.00	**0.728**			VA05082980	0.54
1	4	2.0	2.0	25		0.0				0.0																			
2	1	1.0	1.5	25	5	1.0	q/cb/s	3	1		1.0							2.0				B364867	252.00	252.98	**4.640**			VA05082980	0.98
2	1	1.0	2.0	30		2.0	q/s/cb	3			6.0											B364868	252.98	254.51	**0.053**			VA05082980	1.53
2	1	1.0	2.0	30		2.0	q/s/cb	3			6.0											B364869	252.98	254.51	**0.095**	PD/CA		VA05082980	1.53
																						B364870	STANDARD 2B		**2.960**	2B		VA05082980	
3	1	1.0	3.0	60	25					1.0								5.0				B364871	254.51	256.03	**0.069**			VA05082980	1.52
4	1	1.0	3.5	30		2.0	q/cb/s	3		2.0	2.0							5.0	2.0			B364872	256.03	257.56	**0.020**			VA05082980	1.53
3	1	0.5	1.3	25		4.0	q/cb/s	3		5.0								5.0				B364873	257.56	259.08	**0.150**			VA05082980	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-306C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1116m

BEARING: 000 | DIP: -50°

DATEs DRILLING: Aug 10-17, 2005

DATES LOGGING: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459954 NORTHING: 7099196

COORD SYSTEM: NAD 83: EASTING: 459834 NORTHING: 7099383

NAD 27 (CORRECTED for historic grid): EASTING: 459924 NORTHING: 7099206

SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 33 ft (10.06m)

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B365317 - B365367

Requisition #: MASP448STRGOL.05Q Date Shipped: 9-Sept-05

Lab Record #: VA05080587 Date Received: 20-Sept-05

Sample Sequence: B365368 - B365547

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Sept-05

Lab Record #: VA05083939 Date Received: 28-Sept-05

Duplicates:	365322; 365342; 365362; 365382; 365402; 365422; 365442; 365462; 365482; 365502; 365522; 365542
Preparation Duplicate/ Check Assay:	365329; 365349; 365369; 365389; 365409; 365429; 365449; 365469; 365489; 365509; 365529
Standards:	365330 (3C); 365350 (2B); 365370 (4D); 365390 (1A); 365410 (5E); 365430 (6F); 365450 (3C); 365470 (2B); 365490 (4D); 365510 (5E); 365530 (7G)
Blanks:	365336; 365356; 365376; 365396; 365416; 365436; 365456; 365476; 365496; 365516; 365536

FROM	TO	LITHOLOGY
0.00	10.06	Csg; No recovery
10.06	271.27	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	335.9	-48.0	001.9	002.9
121.91	337.7	-48.9	003.7	004.7
182.87	337.2	-49.0	003.2	004.2
271.26	334.5	-48.2	000.5	001.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 1 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 10.06	0.00	10.06	Casing - No recovery						
10	10.06 - 271.27	10.06	19.81	GND: Unaltered portions of core is typical grey GND; Oxidation is pervasive throughout interval; Where previous alteration selvages occur, oxidation/limonite is much more intensive; Fractures/fracture faces contain calcite/carb and is also very limonitic; Siderite is common within fractures; Core is moderately broken up/fractured - 9cm average length with low angle fracturing (15-45°); Quartz veins contain vugs stained with limonite; Clay alteration occurs locally at 14 - 14.2m with dark rusty red-brown foliation at 45°; Unaltered GND from 17.9 - 18.25m (gradual contact).	4					
10		19.81	28.96	GND: GND is very clay altered and limonitic; full diameter core is rare, most core is extremely crumbly; Carbonate is present throughout core but not abundant; It's difficult to identify fracturing; No recovery from 21.34 - 22.86m.	4			5		
10		28.96	73.15	GND: GND is similar as previously described from interval 10.0 - 19.81m; @ 40.25m, a 0.4cm quartz vein contains blebs of a black massive, soft mineral with a black, slightly shiny, streak - possibly chalcocite?; It is common to see fresh fine grained speckled biotite on calcite fracture faces; Unaltered GND from 50.68 - 50.98m and 51.38 - 51.82m with fresh quartz veins (2% po); Intervals 59.44 - 60.96m (B365357) & 60.96 - 62.48m (B365358) are heavily fractured; Full diameter core is very rare; Limonite, calcite and speckled biotite on most faces.	3					

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.6	1.1	45														2.0				B365317	10.00	10.67	1.315			VA05080587	0.67
2	1	1.2	1.6	45		0.3	q	5	4									4.0				B365318	10.67	12.19	0.186			VA05080587	1.52
4	1	0.6	2.0	40														2.0				B365319	12.19	13.72	0.112			VA05080587	1.53
3	1	0.5	1.3	50	40	0.3	q	5	4									2.0				B365320	13.72	15.24	0.091			VA05080587	1.52
4	1	0.7	1.4	45		1.0	q	5	4									5.0				B365321	15.24	16.76	0.071			VA05080587	1.52
4	1	0.7	1.4	45		1.0	q	5	4									5.0				B365322	15.24	16.76	0.070	DUP		VA05080587	1.52
3	1	1.2	2.8	45		1.0	q	3	4									5.0				B365323	16.76	18.29	0.022			VA05080587	1.53
0																						B365324	18.29	19.81	0.138			VA05080587	1.52
0																						B365325	19.81	21.34	0.013			VA05080587	1.53
0																						B365326	21.34	24.38	0.014			VA05080587	3.04
2	1	0.5	0.7	60														2.0				B365327	24.38	25.91	0.022			VA05080587	1.53
0																						B365328	25.91	27.43	0.071			VA05080587	1.52
0																						B365329	25.91	27.43	0.169	PD/CA		VA05080587	1.52
																						B365330	STANDARD 3C		0.091	3C		VA05080587	
0																						B365331	27.43	28.96	0.358			VA05080587	1.53
3	1	0.5	1.5	45		0.3	q	5	4									2.0				B365332	28.96	30.48	0.044			VA05080587	1.52
5	1	0.7	2.0	45	60	0.5	q	5	4				0.1					4.0				B365333	30.48	32.00	0.515			VA05080587	1.52
4	1	0.4	1.6	45	60	0.3	q	5	4									5.0				B365334	32.00	33.53	0.109			VA05080587	1.53
4	1	0.5	1.2	30		0.3	q	5	4									5.0				B365335	33.53	35.05	0.088			VA05080587	1.52
																						B365336	BLANK		<0.005			VA05080587	
3	1	0.4	0.4	40		0.3	q	5	3									2.0				B365337	35.05	36.58	0.331			VA05080587	1.53
3	1	0.4	1.2			0.2	q	5	3	0.1								2.0				B365338	36.58	38.10	0.717			VA05080587	1.52
1	1	0.6	0.6	40														5.0				B365339	38.10	39.62	0.439			VA05080587	1.52
5	1	0.7	2.4	40		0.3	q	5	3		0.1		0.1				1.0	5.0				B365340	39.62	41.15	0.175		Chalcocite	VA05080587	1.53
6	1	0.6	30.0	55		0.3	q	5	4		0.1							10.0				B365341	41.15	42.67	0.290			VA05080587	1.52
6	1	0.6	30.0	55		0.3	q	5	4		0.1							10.0				B365342	41.15	42.67	0.137	DUP		VA05080587	1.52
5	1	0.5	1.6	30		0.3	q	4	2									5.0				B365343	42.67	44.20	0.171			VA05080587	1.53
4	1	1.0	2.2	30	60	0.3	q	5	4				0.1				1.0	5.0				B365344	44.20	45.72	0.373		Chalcocite	VA05080587	1.52
2	1	0.6	0.8	30		0.3	q	5	3								0.1					B365345	45.72	47.24	0.106		Chalcocite	VA05080587	1.52
2	1	0.4	0.7	30	60													2.0				B365346	47.24	48.77	0.050			VA05080587	1.53
5	1	0.6	18.0	30									0.1				0.1					B365347	48.77	50.29	0.082			VA05080587	1.52
4	1	0.3	1.1	30	40						2.0											B365348	50.29	51.82	0.065			VA05080587	1.53
4	1	0.3	1.1	30	40						2.0											B365349	50.29	51.82	0.092	PD/CA		VA05080587	1.53
																						B365350	STANDARD 2B		3.090	2B		VA05080587	
3	1	0.5	1.2	30							0.1							4.0				B365351	51.82	53.34	0.103			VA05080587	1.52
1	1	0.3	0.3	35														2.0				B365352	53.34	54.86	0.023			VA05080587	1.52
0																						B365353	54.86	56.39	0.054			VA05080587	1.53
3	1	1.0	2.2	30														2.0				B365354	56.39	57.91	0.023			VA05080587	1.52
1	1	0.4	0.4	45									0.1					2.0				B365355	57.91	59.44	0.100			VA05080587	1.53
																						B365356	BLANK		<0.005			VA05080587	
2	1	0.2	0.4	30	45												0.1	2.0				B365357	59.44	60.96	0.034		Chalcocite?	VA05080587	1.52
0																						B365358	60.96	62.48	0.040			VA05080587	1.52
2	1	0.4	0.8	40														2.0				B365359	62.48	64.01	0.041			VA05080587	1.53
1	1	0.6	0.6	40													0.1	2.0				B365360	64.01	65.53	0.024			VA05080587	1.52
1	3	0.3	0.3	40																									
0																						B365361	65.53	67.06	0.060			VA05080587	1.53
0																						B365362	65.53	67.06	0.019	DUP		VA05080587	1.53

DRILL HOLE # : DG05-306C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		73.15	88.39	GND: GND similar to previous, except GND is more heavily fractured; Broken blocks are angular with an average size of 5x3x3cm; Random blocks of full diameter core up to 15cm; Slickenlines: @81.27m face at 40° with lines at 40°; @ 85.30m 55°/65° TCA.	3					
10		88.39	92.96	GND: GND is relatively unaltered, minor limonite occurs locally throughout core in intervals up to 25cm; Limonite is also present where local quartz flooding occurs (silicified core); Limonitic interval contacts are gradual (rarely sharp): GND is competent.	1					
10		92.96	108.82	GND: GND is same as previously described in interval 10.0 - 19.81m; From 100.45 - 100.55m core is extremely carb altered and clay alt'd and very limonitic; Slickenlines: @ 94.38m = 2°/60° TCA; @ 106.6m broken, angular clocks of MSED occur. Thickness of MSED cannot be determined (<25cm); Various blocks show a sharp contact with GND at 15°-20°. MSED consists of black and light brown bedding/foliation.	3					
10		108.82	118.87	GND: GND similar to previous from intervals 88.39 - 92.96m	2					
10		118.87	125.21	GND: GND has been intensely sericite altered and oxidized; Locally core has been very clay altered as well; Where sericite and clay alteration is most intense, carbonate alteration is also strong; Core appears brecciated from 119.38 - 119.55m with abundant angular white quartz clasts (1x.5x.5cm avg); Brecciation has sharp up hole contact with white quartz vein (3.5cm) and shear zone at 30° TCA; Breccia matrix is very limonitic with abundant smaller quartz clasts (2x2x3mm avg), no carb alteration is observed; Shear zone contains major elongate v f gr massive pyrite along foliation at 20° and 60° TCA; Matrix consists of small quartz eyes (2x2x2mm) and sericitized GND; Throughout SHEAR ZONE are large vugs (up to 3x3x1.5cm) stained with limonite, perhaps due to brecciation or oxidation of sulphides.	5	5				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.4	0.4	40														2.0				B365363	67.06	68.58	**0.057**			VA05080587	1.52
2	1	0.6	1.2	40														3.0				B365364	68.58	70.10	**0.030**			VA05080587	1.52
4	1	0.4	1.1	60	30	0.4	s	5	4				0.1					5.0				B365365	70.10	71.63	**0.221**			VA05080587	1.53
0																						B365366	71.63	73.15	**0.056**			VA05080587	1.52
2	1	0.5	1.0	45														1.0				B365367	73.15	74.68	**0.031**			VA05080587	1.53
1	1	0.5	0.5	45														4.0				B365368	74.68	76.20	**0.023**			VA05083939	1.52
1	1	0.5	0.5	45														4.0				B365369	74.68	76.20	**0.033**	PD/CA		VA05083939	1.52
																						B365370	STANDARD 4D		**0.451**	4D		VA05083939	
0																						B365371	76.20	77.72	**0.025**			VA05083939	1.52
0																						B365372	77.72	79.25	**0.009**			VA05083939	1.53
1	1	0.5	0.5	45														2.0				B365373	79.25	80.77	**0.022**			VA05083939	1.52
1	1	0.4	0.4	45														2.0				B365374	80.77	82.30	**0.024**			VA05083939	1.53
1	1	0.4	0.4	40														2.0				B365375	82.30	83.82	**0.019**			VA05083939	1.52
																						B365376	BLANK		**<0.005**			VA05083939	
1	1	0.4	0.4	45														5.0				B365377	83.82	85.34	**0.025**			VA05083939	1.52
0																						B365378	85.34	86.87	**0.028**			VA05083939	1.53
1	1	0.2	0.2	45														2.0				B365379	86.87	88.39	**0.018**			VA05083939	1.52
3	1	0.5	1.2	45		0.2	q	5	3	10.0												B365380	88.39	89.92	**0.814**			VA05083939	1.53
1	1	0.4	0.4	45		0.4	s	3	1									1.0				B365381	89.92	91.44	**0.022**			VA05083939	1.52
1	1	0.4	0.4	45		0.4	s	3	1									1.0				B365382	89.92	91.44	**0.043**	DUP		VA05083939	1.52
0																						B365383	91.44	92.96	**0.025**			VA05083939	1.52
2	1	1.0	1.5	45														5.0				B365384	92.96	94.49	**0.077**			VA05083939	1.53
0																						B365385	94.49	96.01	**0.025**			VA05083939	1.52
0																						B365386	96.01	97.54	**0.096**			VA05083939	1.53
3	1	0.4	1.1	30	45								0.1					2.0				B365387	97.54	99.06	**0.189**			VA05083939	1.52
1	1	0.3	0.3	30		0.2	q	5	4									1.0				B365388	99.06	100.58	**0.479**			VA05083939	1.52
1	1	0.3	0.3	30		0.2	q	5	4									1.0				B365389	99.06	100.58	**0.298**	PD/CA		VA05083939	1.52
																						B365390	STANDARD 1A		**0.957**	1A		VA05083939	
1	1	0.4	0.4	40																		B365391	100.58	102.11	**0.047**			VA05083939	1.53
3	1	1.0	2.5	60	30	0.3	q	5	3									2.0				B365392	102.11	103.63	**0.147**			VA05083939	1.52
0																						B365393	103.63	105.16	**0.085**			VA05083939	1.53
1	1	1.5	1.5	60														2.0				B365394	105.16	106.68	**0.019**			VA05083939	1.52
2	1	0.3	0.6	60	30								1.0					2.0				B365395	106.68	108.20	**0.031**			VA05083939	1.52
																						B365396	BLANK		**<0.005**			VA05083939	
2	1	1.0	2.0	30		0.3	q	5	3									2.0				B365397	108.20	108.82	**0.034**			VA05083939	0.62
2	5	0.3	0.5	45	30	0.4	q	3	2													B365398	108.82	109.73	**0.039**			VA05083939	0.91
1	1	0.2	0.2	45		0.3	q	5			5.0																			
4	1	0.4	1.2	45	30						1.0	0.1	0.1					2.0				B365399	109.73	111.25	**0.108**			VA05083939	1.52
1	1	1.0	1.0	45																		B365400	111.25	112.78	**0.029**			VA05083939	1.53
1	5	0.3	0.3	40																										
6	1	1.2	2.8	60	40	0.4	q	5	3				0.1					2.0				B365401	112.78	114.30	**0.093**			VA05083939	1.52
6	1	1.2	2.8	60	40	0.4	q	5	3				0.1					2.0				B365402	112.78	114.30	**0.038**	DUP		VA05083939	1.52
1	1	1.0	1.0	40		0.3	q	5			2.0											B365403	114.30	115.82	**0.213**			VA05083939	1.52
4	1	1.0	1.8	30	45						1.0		1.0					1.0				B365404	115.82	117.35	**0.021**			VA05083939	1.53
4	1	1.0	2.6	30							1.0							2.0				B365405	117.35	118.87	**0.225**			VA05083939	1.52
0																						B365406	118.87	119.34	**0.074**			VA05083939	0.47

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 5 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.21	131.06	GND: Unaltered GND with slight oxidation, same as described from interval 88.39 - 92.96m; Slickenlines: @130.9m = face at 30° and lines at 60°.	1					
10		131.06	143.26	GND: GND is moderately clay altered through out most of the interval; Oxidation is pervasive throughout as well; Core appears much lighter in colour; Core is heavily fractured from 131.06 - 132.15m and 140.21 - 141.3m; Clay alteration tends to be more intense where core is heavily fractured; Quartz veining still commonly vuggy and stained with limonite; @ 140.4m minor shear zone (~5cm) with foliation at 20°. Shear zone consists of sericite altered matrix with small quartz eyes (2x2x2mm) and massive, black, clayey pyrite.	4			3		
10		143.26	156.97	GND: Unaltered God same as previously described from 88.39 - 92.96m; Oxidation only along fractures/fracture faces except locally at 148.86 - 149.35m where GND is moderately oxidized throughout; From 153.01 - 153.76m GND is moderately clay altered (3) and paler; Abundant calcitic fractures throughout; Evidence of quartz veining but veins too broken/irregular to measure; No foliation. Slickenlines: @149.33m face at 30° with lines at 45°; @ 150.8m 30°/45°; @ 151.65m 60°/75° TCA.	1					
10		156.97	163.07	GND: Unaltered grey GND; Rare limonite on fractures; Fracture faces/fills still contain calcite but now seeing sericite selvages up to 8cm (non-oxidized); Fracture faces also have darker green mineral (chl?) with calcite; Quartz veining becoming more abundant; @ 157.08m, 0.8cm quartz vein displays 2.5cm sinistral displacement by calcite filled fractures; Slickenlines: @158.48m, face at 20° with lines at 30° TCA; @ 159.05m, face at 30° with lines at 60°; @ 159.45m, face at 2° with lines at 45° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	3.5	3.5	30									5.0									B365407	119.34	119.69	**33.800**			VA05083939	0.35
1	1	0.4	0.4	30																		B365408	119.69	120.40	**0.052**			VA05083939	0.71
1	1	0.4	0.4	30																		B365409	119.69	120.40	**0.048**	PD/CA		VA05083939	0.71
																						B365410	STANDARD 5E		**1.495**	5E		VA05083939	
3	1	1.2	2.2	30						1.0												B365411	120.40	121.92	**0.045**			VA05083939	1.52
2	1	9.0	9.5	50						2.0								1.0				B365412	121.92	123.44	**0.095**			VA05083939	1.52
3	1	1.0	1.6	25									0.1					2.0				B365413	123.44	125.21	**0.074**			VA05083939	1.77
2	1	1.4	2.4	25														1.0				B365414	125.21	126.49	**0.034**			VA05083939	1.28
1	1	0.5	0.5	30														1.0				B365415	126.49	128.02	**0.047**			VA05083939	1.53
																						B365416	BLANK		**<0.005**			VA05083939	
4	1	0.5	1.8	30						1.0	1.0											B365417	128.02	129.54	**0.010**			VA05083939	1.52
4	1	0.7	1.7	30							5.0	0.1	1.0									B365418	129.54	131.06	**0.045**			VA05083939	1.52
2	1	1.0	1.5	40														1.0				B365419	131.06	132.59	**0.058**			VA05083939	1.53
2	1	1.0	2.0	30														1.0				B365420	132.59	134.11	**0.141**			VA05083939	1.52
1	6	0.5	0.5	10						90.0																				
4	1	3.5	5.0	30	60													1.0				B365421	134.11	135.64	**0.090**			VA05083939	1.53
4	1	3.5	5.0	30	60													1.0				B365422	134.11	135.64	**0.177**	DUP		VA05083939	1.53
2	1	0.8	1.4	30														1.0				B365423	135.64	137.16	**0.060**			VA05083939	1.52
3	1	1.2	2.2	30	45													2.0				B365424	137.16	138.68	**0.208**			VA05083939	1.52
1	1	0.4	0.4	30														1.0				B365425	138.68	140.21	**0.027**			VA05083939	1.53
0																						B365426	140.21	141.73	**0.483**			VA05083939	1.52
1	1	1.0	1.0	30																		B365427	141.73	143.26	**0.035**			VA05083939	1.53
4	1	1.7	4.1	30	45						1.0		0.1					1.0				B365428	143.26	144.78	**0.035**			VA05083939	1.52
4	1	1.7	4.1	30	45						1.0		0.1					1.0				B365429	143.26	144.78	**0.042**	PD/CA		VA05083939	1.52
																						B365430	STANDARD 6F		**2.810**	6F		VA05083939	
4	1	0.5	1.5	30							1.0		1.0				1.0					B365431	144.78	146.30	**0.074**		Calcite?	VA05083939	1.52
2	1	0.5	0.8	30		0.2	q/s	4	1		1.0		1.0									B365432	146.30	147.83	**0.086**			VA05083939	1.53
5	1	0.5	2.0	30		0.4	q/s	5	2		1.0	0.1	2.0									B365433	147.83	149.35	**0.099**			VA05083939	1.52
5	1	2.5	3.6	30	40	0.5	q/s	5	2	10.0	1.0	0.1	4.0									B365434	149.35	150.88	**0.185**			VA05083939	1.53
1	1	0.2	0.2	40	40	0.2	q/s	5	0		0.1											B365435	150.88	152.40	**0.018**			VA05083939	1.52
1	5	0.2	0.2	30	30								5.0																
																						B365436	BLANK		**<0.005**			VA05083939	
																						B365437	152.40	153.01	**0.016**			VA05083939	0.61
0																						B365438	153.01	153.76	**0.162**			VA05083939	0.75
0																						B365439	153.76	155.45	**0.269**			VA05083939	1.69
2	1	2.0	2.5	45	30						0.1																			
2	5	0.4	0.7	40							2.0		2.0									B365440	155.45	156.97	**0.642**			VA05083939	1.52
1	1	0.5	0.5	45																										
1	6	0.4	0.4	40		0.5	q	4					40.0																	
7	1	0.8	2.8	30	40	0.3	q	5		2.0	5.0	0.1	2.0									B365441	156.97	158.50	**0.133**		QV with py is within ser frac selvage	VA05083939	1.53
1	6	0.2	0.2	40		0.5	q	5			20.0		2.0																	
7	1	0.8	2.8	30	40	0.3	q	5		2.0	5.0	0.1	2.0									B365442	156.97	158.50	**0.182**	DUP	QV with py is within ser frac selvage	VA05083939	1.53
1	6	0.2	0.2	40		0.5	q	5			20.0		2.0																	
1	1	0.6	0.6	60							1.0	0.1	2.0									B365443	158.50	160.02	**0.023**			VA05083939	1.52
1	1	1.5	1.5	35						1.0	1.0											B365444	160.02	161.54	**17.200**		QV has 1mm envelope of cb/chl	VA05083939	1.52
5	1	0.5	2.5	35		1.0	s	4			2.0		1.0									B365445	161.54	163.07	**0.144**			VA05083939	1.53

DRILL LOG LEGEND - P1	DATE: September 2 - 5, 2005 PAGE 7 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		163.07	170.69	GND: Grey GND is softer and slightly lighter in colour due to clay alteration; For the most part, core is competent except locally where it is moderately oxidized and heavily fractured with carb/calcite filled fracts from 164.59 - 165.65m and 166.52 167.64m; Shear zones tend to be more intensely clay altered and have dull grey clay zones along the foliation; Quartz eyes within shear zones are brittle and slightly softer; Shear zones: @163.37 - 163.42m at 50°; @ 164.08 - 164.17m at 70°; @ 167.8 - 167.90m at 35°; Dull grey clay stringers (whitish streaks) commonly contain v f gr py disseminated throughout; Slickenlines: @166.15m face at 40° with lines at 45°; @ 167.0m face at 10° with lines at 60°; @ 168.0m face at 30° with lines at 45° TCA.				3		
10		170.69	178.50	GND; GND is only slightly clay altered, slightly lighter grey than grey GND; Calcite fill fractures throughout; Limonitic fractures approx 60%, decreasing down hole; Intense clay alteration occurs locally from 175.2 - 175.36m and 178.25 - 178.38m; <1mm veinlets consisting of chlorite and carbonate are common with po, and at various angles; Slickenlines: @ 174.45m face at 5° with lines at 1°; @ 175.56m face at 30° with lines at 40° TCA.				1		
10		178.50	190.50	GND: Unaltered GND with small intervals of sericite alteration; Same as previously described (156.97 - 163.07m), though no limonite on fractures; Smeared pyrite common along slip faces; Slickenlines: @ 179.7m, face at 15° with lines at 15°; @ @ 182.38m face at 60° with lines at 2°; @ 182.4m face at 30° with lines at 40°; @ 186.05m face at 30° with lines at 45°; @ 186.68m face at 45° with lines at 5° TCA.						
10		190.50	198.12	GND: GND has undergone chlorite and sericite alteration; Sericite alteration is more abundant throughout intervals; Sections of only slight sericite alteration occur from 194.36 - 195.0m and 195.0 - 195.42m; Chlorite alteration is most abundant up hole; Where only sericite alteration occurs, euh-subhed grains of k-spar (up to 4x2.5mm) are speckaled throughout as well as <1mm veinlets of k-spar; From 190.5 - 191.07m (B365472), 2 quartz veins occur...one thick (>10cm) white with down ctc at 45° TCA, containing fine to med gr euhedral pyrite; Other vein 1.8cm thick, containing abundant v f gr massive py as stringers and blebs throughout; Minor SHEAR ZONE/FAULT GOUGE at 193.29m at 70° TCA (1.5cm); @ 197.95m, 2 quartz veins at 80° are offset 1cm by a dextral motion by 5° fracture containing v f gr py; Slickenlines: @ 194.3m, face at 20° with lines at 50° TCA; @ 196.9m, face at 70° with lines at 2°; @ 197.05m face at 80° with lines at 90° TCA.		5	3			3

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	5	0.3	0.3	35		0.5	q	5			5.0																		
0																						B365446	163.07	164.59	0.309			VA05083939	1.52
2	1	2.5	4.6	50						1.0			0.1					1.0				B365447	164.59	165.65	0.119			VA05083939	1.06
1	1	0.7	0.7	50						1.0								1.0				B365448	165.65	166.52	0.140			VA05083939	0.87
1	1	0.7	0.7	50						1.0								1.0				B365449	165.65	166.52	0.038	PD/CA		VA05083939	0.87
																						B365450	STANDARD 3C		0.101	3C		VA05083939	
0																						B365451	166.52	167.64	0.085			VA05083939	1.12
2	1	0.6	1.2	30	45																	B365452	167.64	169.16	0.787			VA05083939	1.52
2	1	2.0	3.0	65																		B365453	169.16	170.69	0.063			VA05083939	1.53
3	1	1.0	2.0	35		0.6	q	5		3.0	4.0	0.1	2.0									B365454	170.69	172.21	0.313			VA05083939	1.52
1	1	0.4	0.4	35							10.0	2.0										B365455	172.21	173.74	0.023			VA05083939	1.53
																						B365456	BLANK		<0.005			VA05083939	
0																						B365457	173.74	174.86	0.029			VA05083939	1.12
0																						B365458	174.86	175.49	0.983			VA05083939	0.63
1	1	0.5	0.5	50																		B365459	175.49	177.05	0.330			VA05083939	1.56
4	1	0.8	2.2	30		2.0	q/chl	4		0.1	3.0											B365460	177.05	178.50	0.065		Py found in cb bleb within QV	VA05083939	1.45
1	1	0.4	0.4	35							1.0											B365461	178.50	179.83	0.097			VA05083939	1.33
1	1	0.4	0.4	35							1.0											B365462	178.50	179.83	0.066	DUP		VA05083939	1.33
1	1	0.2	0.2	35							1.0											B365463	179.83	181.36	0.030			VA05083939	1.53
4	1	0.5	2.0	40						1.0	2.0											B365464	181.36	182.88	0.200			VA05083939	1.52
1	6	0.4	0.4			0.3	q	5			15.0																		
0																						B365465	182.88	184.40	0.357			VA05083939	1.52
1	1	0.4	0.4	35							1.0											B365466	184.40	185.93	0.010			VA05083939	1.53
1	1	0.4	0.4	40							2.0											B365467	185.93	187.45	0.063			VA05083939	1.52
3	1	0.8	1.8	40	45						1.0	0.1										B365468	187.45	188.98	0.047			VA05083939	1.53
3	1	0.8	1.8	40	45						1.0	0.1										B365469	187.45	188.98	0.053	PD/CA		VA05083939	1.53
																						B365470	STANDARD 2B		3.180	2B		VA05083939	
1	1	0.4	0.4	40							1.0											B365471	188.98	190.50	0.113			VA05083939	1.52
2	1	10.0	11.8	45						5.0			1.0									B365472	190.50	191.07	5.000			VA05083939	0.57
2	1	0.4	0.8	30						0.1	2.0											B365473	191.07	192.02	0.239			VA05083939	0.95
2	1	1.2	1.7	60	30						3.0											B365474	192.02	193.55	0.051			VA05083939	1.53
4	1	0.5	1.2	40	10					0.1	2.0											B365475	193.55	195.07	0.174			VA05083939	1.52
																						B365476	BLANK		<0.005			VA05083939	
6	1	0.5	2.5	35						1.0	2.0											B365477	195.07	196.60	0.662			VA05083939	1.53
1	6	0.4	0.4	30						2.0	15.0																		
4	1	1.0	2.8	15	80					1.0	2.0											B365478	196.60	198.12	0.190			VA05083939	1.52

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 9 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		198.12	203.60	GND: GND is slightly sericite altered throughout; Clay alteration gradually increases downhole (1 to 2); A 4cm white quartz vein (@ 30° TCA) is displaced at 201.28m (40°), 201.45m (40°) and 201.62m (70°); @ 201.62m dextral displacement is measured to be 6cm at 70° with 0.8cm fault gg; @ 199.6m, a 3cm white quartz vein with large massive pyrrhotite blebs (4x2cm); Slickenlines: @199.54m the fracture face is at 60° with lines at 90° TCA: @ 200.00m the face is at 1° with lines at 1°.		2		1		
10		203.60	211.84	GND: Core is highly clay altered, moderately sericite altered, and locally clay altered (with more intense clay alteration); @ 203.6 - 205.74m = SHEAR ZONE with low angle foliations (10° - 30° and 60°), containing angular quartz veins clasts (white) up to 3x3cm. Also abundant small quartz eyes throughout, soft sericitized, clay altered matrix with carbonate; Quartz vein in shear zone displaced and broken up; Slickenlines: @ 205.5m, face at 5° with lines at 30°; @ 210.85m face at 30° with lines at 85°.		3		5	3	
10		211.84	224.03	GND: GND is intensely sericite altered as previous interval but clay alteration is less extensive (intervals up to 40cm); Where clay alteration is most intensive, carb alteration occurs (small gm-gy clay); Massive py from 220.61 - 220.72m; From 221.38 - 221.82m core appears brecciated with white quartz vein clasts and irregular/displaced quartz veins. Fine to med gr euhedral py is disseminated throughout; K-spar grains (eu-subhed) and vnlts throughout tend to be softer and slightly carb alt'd; K-spar veinlets and euhedral, speckled grains become more abundant down hole; Slickenlines: @212.39m - face at 45° with lines at 5°; @ 212.8m face at 45° with lines at 85°.		5		3		
10		224.03	258.52	GND: Slight ser alteration; Locally, intense sericite alteration with euh-subhed k-spar grains and vnlts (228.6 - 228.86m, 229.3 - 229.45m, 232.7 - 233.0m, 234.75 - 235.35m, 239.27 - 239.94m, 244.37 - 245.71m - 247.47 - 247.91m and 250.18 - 259.41m); Fracture faces are chl/ser altered with carb/calcite; From 235.15 - 235.35m sericite core appears brecciated; Core is competent with abnt k-spar vnlts (mm to 1.7cm); Fine - C gr py blebs also abndt (~15%); Large massive spy bleb (2.5x1cm) present (~5% of breccia zone); Breccia zone has sharp contact with 70% f gr py and 20% k-spar; From 240.4 - 240.94m MGD is present with sharp contact to unaltered grey GND at 5° TCA; Slickenlines: @233.2 = 40°/80°; @ 233.3m = 70°/5°; @ 235.17m = 80°/5°; @ 240.25m = 20°/75°; @ 245.6m = 80°/5°; @ 246.49m = 45°/45°; @ 248.2m = 30°/90°; @ 249.3m = 40°/75°; @ 249.42m = 5°/60°; @ 249.42m = 85°/85° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	3.0	5.8	60	45					0.1	5.0											B365479	198.12	199.64	1.040			VA05083939	1.52
4	1	0.8	2.4	60							1.0											B365480	199.64	201.17	0.286			VA05083939	1.53
2	1	4.0	6.0	30	15					1.0	2.0											B365481	201.17	202.30	0.153			VA05083939	1.13
2	1	4.0	6.0	30	15					1.0	2.0											B365482	201.17	202.30	0.105	DUP		VA05083939	1.13
1	1	0.3	0.3	60							2.0											B365483	202.30	203.60	0.231			VA05083939	1.30
3	1	1.0	3.0	60																		B365484	203.60	204.22	0.064			VA05083939	0.62
0																						B365485	204.22	205.74	1.010			VA05083939	1.52
2	1	0.5	0.8	15	60					2.0												B365486	205.74	207.26	0.559			VA05083939	1.52
0																						B365487	207.26	208.79	0.400			VA05083939	1.53
1	1	0.4	0.4	60							1.0											B365488	208.79	210.31	0.060			VA05083939	1.52
1	1	0.4	0.4	60							1.0											B365489	208.79	210.31	0.049	PD/CA		VA05083939	1.52
																						B365490	STANDARD 4D		0.444	4D		VA05083939	
0																						B365491	210.31	211.48	0.024			VA05083939	1.17
3	1	1.5	2.2	60	45					1.0	1.0											B365492	211.48	213.36	0.142			VA05083939	1.88
1	1	1.2	1.2	60						3.0												B365493	213.36	214.88	0.163			VA05083939	1.52
1	1	0.4	0.4	60							2.0											B365494	214.88	216.41	0.136			VA05083939	1.53
1	3	0.3	0.3	60																									
2	1	0.2	0.4	60							2.0											B365495	216.41	217.93	0.111			VA05083939	1.52
																						B365496	BLANK		<0.005			VA05083939	
1	1	0.4	0.4	65		2.0	k/s	5														B365497	217.93	219.46	0.078			VA05083939	1.53
1	2	1.8	1.8	70						5.0																			
0																						B365498	219.46	220.10	0.270			VA05083939	0.64
4	1	14.0	23.0	45	60					5.0												B365499	220.10	220.98	4.330			VA05083939	0.88
1	6	8.0	8.0	45						80.0																			
2	1	10.0	11.0	80	5					8.0												B365500	220.98	222.50	0.881			VA05083939	1.52
6	1	1.0	2.5	70						5.0												B365501	222.50	224.03	0.072			VA05083939	1.53
1	2	0.4	0.4	70																									
1	6	0.5	0.5	70						90.0																			
6	1	1.0	2.5	70						5.0												B365502	222.50	224.03	0.067	DUP		VA05083939	1.53
1	2	0.4	0.4	70																									
1	6	0.5	0.5	70						90.0																			
8	1	0.6	3.0	70		2.0	5	5		1.0	4.0											B365503	224.03	225.55	0.296			VA05083939	1.52
2	1	0.3	0.6	70							1.0											B365504	225.55	227.08	0.157			VA05083939	1.53
6	1	1.2	4.5	70	40						1.0											B365505	227.08	228.60	0.098			VA05083939	1.52
2	1	0.4	0.6	70							1.0											B365506	228.60	230.12	0.099			VA05083939	1.52
3	1	0.5	1.5	70							2.0											B365507	230.12	231.65	0.313			VA05083939	1.53
3	1	1.0	3.0	70							1.0											B365508	231.65	233.17	0.069			VA05083939	1.52
3	1	1.0	3.0	70							1.0											B365509	231.65	233.17	0.060	PD/CA		VA05083939	1.52
																						B365510	STANDARD 5E		1.435	5E		VA05083939	

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		251.71	258.52	GND: Fine grained Quartz-rich granitoid (GND?); Sericite altered; Irregular k-spar veinlets throughout; Quartz vein at 256.43m (50°) shows dextral displacement (0.4cm) along 60° fracture; Sharp up-hole contact adjacent to quartz veins at 55°; Down hole ctc is sharp and irregular, greyish-white quartz vein crosscuts ctc at 60°; Pyrite smearing on slip faces common; Slickenlines: @ 251.80m = 70°/80°; @ 252.6m = 25°/70°; @ 255.28m = 60°/70°; @ 256.1m = 20°/85°.		5				
10		258.52	271.27	GND: GND has been intensely altered with abundant k-spar (propylitic alt'n); Intervals of unaltered grey GND locally; From 260.09 - 260.47m core appears greyish-green and is very hard (possible silicification followed by sericite alt'n), similarly between 261.89 - 262.13m and 202.8 - 263.0m; Locally core is heavily fractured (263.0 - 263.45m) with carbonate and ser/chlorite on fracture faces; Slickenlines: @ 262.33m = 20°/10°; 263.70m = 50°/5° TCA.		5				4

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
4	1	0.8	2.1	70							1.0	0.1										B365511	233.17	234.87	**0.402**			VA05083939	1.70
1	1	0.4	0.4	50																		B365512	234.87	235.35	**0.383**			VA05083939	0.48
2	2	0.5	1.0	80																									
1	1	1.0	1.0	70							1.0											B365513	235.35	236.22	**0.716**			VA05083939	0.87
3	1	0.6	1.2	70							1.0	0.1			0.1							B365514	236.22	237.74	**0.075**			VA05083939	1.52
7	1	0.5	2.2	70							1.0	0.1										B365515	237.74	239.27	**0.133**			VA05083939	1.53
																						B365516	BLANK		**<0.005**			VA05083939	
5	1	1.5	4.3	70	40					1.0	2.0	0.1										B365517	239.27	239.90	**1.910**			VA05083939	0.63
1	2	2.0	2.0	45																									
2	1	0.5	0.7	70		0.3	s	3			2.0											B365518	239.90	240.94	**0.082**			VA05083939	1.04
5	1	0.6	2.0	70	80	1.0	s	3			2.0	0.1										B365519	240.94	242.32	**0.142**			VA05083939	1.38
1	6	0.3	0.3	60							50.0																		
2	1	1.0	2.0	70		2.0	s	5			1.0											B365520	242.32	243.84	**0.363**			VA05083939	1.52
2	1	0.5	0.9	70		0.6	s	5			5.0											B365521	243.84	244.88	**0.062**			VA05083939	1.04
2	1	0.5	0.9	70		0.6	s	5			5.0											B365522	243.84	244.88	**0.032**	DUP		VA05083939	1.04
1	1	1.5	1.5	45																		B365523	244.88	245.80	**0.174**			VA05083939	0.92
2	2	1.0	1.5	70						2.0																			
1	6	0.2	0.2	60						99.0																			
1	1	0.5	0.5	70																		B365524	245.80	246.89	**0.933**			VA05083939	1.09
4	2	0.5	1.2	70						5.0												B365525	246.89	248.11	**0.181**			VA05083939	1.22
1	6	0.2	0.2	80						80.0																			
3	1	0.5	0.5	70							3.0																		
3	1	3.0	6.5	45	70						1.0											B365526	248.11	249.49	**0.112**			VA05083939	1.38
6	2	0.5	3.0	80							0.1											B365527	249.49	251.71	**0.281**			VA05083939	2.22
1	6	1.0	1.0	70						40.0																			
6	1	0.7	2.8	60	45	1.0	s	5		2.0	2.0		0.1									B365528	251.71	252.98	**1.470**			VA05083939	1.27
6	1	0.7	2.8	60	45	1.0	s	5		2.0	2.0		0.1									B365529	251.71	252.98	**1.155**	PD/CA		VA05083939	1.27
																						B365530	STANDARD 7G		**4.470**	7G		VA05083939	
4	1	0.5	1.4	70	50	0.5	s	1		2.0	0.1											B365531	252.98	254.51	**0.297**			VA05083939	1.53
1	6	0.2	0.2	70						90.0																			
2	2	0.3	0.5	45	1	s	3		5																				
1	1	0.5	0.5	60						5.0												B365532	254.51	256.03	**0.207**			VA05083939	1.52
5	1	0.5	2.1	60		1.0	s/k	5		2.0												B365533	256.03	257.56	**0.131**			VA05083939	1.53
7	1	0.6	3.5	60						1.0												B365534	257.56	258.52	**0.128**			VA05083939	0.96
3	1	0.3	0.9	70	45	0.5	s	5		1.0												B365535	258.52	259.08	**0.390**			VA05083939	0.56
																						B365536	BLANK		**<0.005**			VA05083939	
5	1	1.0	5.5	45	70	0.6	s	5		1.0	1.0	0.1										B365537	259.08	260.60	**0.624**			VA05083939	1.52
1	3	0.4	0.4	30		0.4	s	5																					
2	1	0.4	0.7	70	60						1.0											B365538	260.60	262.13	**0.103**			VA05083939	1.53
2	2	0.4	0.8	70																									
2	1	0.4	0.8	60	70						2.0											B365539	262.13	263.00	**0.330**			VA05083939	0.87
1	6	0.4	0.4	60						15.0																			
1	3	1.0	1.0	60						5.0	10.0																		
0																						B365540	263.00	263.45	**0.143**			VA05083939	0.45
1	1	0.5	0.5	30																		B365541	263.45	264.53	**0.356**			VA05083939	1.08
1	1	0.5	0.5	30																		B365542	263.45	264.53	**0.255**	DUP		VA05083939	1.08
2	1	0.7	1.0	30						0.1												B365543	264.53	265.18	**0.198**			VA05083939	0.65
5	1	0.6	2.5	45	60					2.0												B365544	265.18	266.70	**0.639**			VA05083939	1.52
4	1	0.5	1.2	30	70					2.0	1.0		0.1		0.1							B365545	266.70	268.22	**3.410**			VA05083939	1.52
4	1	0.8	2.0	45	70	1.0	s	5			2.0											B365546	268.22	269.75	**0.212**			VA05083939	1.53
5	1	2.5	5.2	30	150					1.0	1.0											B365547	269.75	271.27	**0.103**			VA05083939	1.52

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 13 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date:____September 2 - 5, 2005

LOGGED BY:___Kevin Piepgrass_____

PAGE 14 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	2	0.4	1.0	60	80	2.5	s	5																							
																							EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-307C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1113m

BEARING: 000 | DIP: -50°

DATES DRILLING:	DATES LOGGING:
Aug 17 - 23, 2005	Sept 4 - 8, 2005

LOGGED BY:
Melodie Stone

CONTRACTOR:
Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459956 NORTHING: 7099141
COORD SYSTEM: NAD 83: EASTING: 459837 NORTHING: 7099322
NAD 27 (CORRECTED for historic grid): EASTING: 459926 NORTHING: 7099151
SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ
Overburden:
Deviation:
Casing: 28 ft (8.53m)
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B364874 - B364925
Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Sept-05
Lab Record #: VA05083121 Date Received: 28-Sept-05

Sample Sequence: B364926-B364925
Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05
Lab Record #: VA05082694 Date Received: 27-Sept-05

Sample Sequence: B365026 - B365127
Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05
Lab Record #: VA05082694 Date Received: 27-Sept-05

Duplicates:	364882; 364902; 364922; 364942; 364962; 364982; 365002; 365022; 365042; 365062; 365082; 365102; 365122
Preparation Duplicate/ Check Assay:	364889; 364909; 364929; 364949; 364969; 364989; 365009; 365029; 365049; 365069; 365089; 365109
Standards:	364890 (4D); 364910 (7G); 364930 (3C); 364950 (1A); 364970 (5E); 364990 (7G); 365010 (6F); 365030 (2B); 365050 (5E); 365070 (6F); 365090 (4D); 365110 (1A)
Blanks:	364876; 364896; 364916; 364936; 364956; 364976; 364996; 365016; 365036; 365056; 365076; 365096; 365116

FROM	TO	LITHOLOGY
6.71	291.08	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
30.48	335.3	-48.5	001.3	002.3
99.06	336.6	-46.8	002.6	003.6
190.49	336.5	-45.4	002.5	003.5
291.07	335.7	-44.0	001.7	002.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 1 of 14											
DRILL HOLE # : DG05-307C	FeOx 0 = Unoxidized 5 = Intensely Ox'd		Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered				Carbonate 0 = No Effervescence 5 = Strong Effervescence					
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93												
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)							
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other		
-1	0.00 - 6.71	0.00	6.71	Casing								
10	6.71 - 291.08	6.71	38.10	GND: Pervasively moderately oxidized GND, such that overall colour is medium greyish brown; GND texture medium grained; Throughout section, there are ≥1cm quartz veins and grouped 0.5cm quartz veins with minimal mineralization, all oxidized or altered to biotite; Selvages are carb-quartz altered and small; @27m one 10cm zone of pervasive alteration includes sericite, silicification, muscovite and rusty oxidized hematite, 0.4cm in width, 3cm long.	3	0	0	1	2			
10		38.10	61.18	GND: GND even more oxidized, broken up to crumbly; Recovery moderate; Veins continue but are less visible due to amount of breakage; Veins contain greater concentration (up to 5%) of oxidized hematite and ~2% of massive metallic silver to tarnished black sulphide (chromite?), soft; @ 50.5m a 40cm zone of silicification and carbonitization (totally oxidized) surrounds 2 quartz veins and one carbonate veinlet. This same alteration forms wide selvages (~10cm, avg) around veinlets of carbonate and oxidized pyrite (? black, opaque), often breaking at veinlet; Larger quartz veins often have ~2% open space where it appears minerals have weathered away or 'popped' out during transport; @ 54.2m a zone of carbonate-rich oxidized clay/fault gouge appears, texture fine sand (<1mm).	4	0	0	1	3			
10		61.18	86.87	GND: Very crumbly section; Oxidation/limonite continues. 10% of section is in pieces <1cm, down to fine sand; Maximum length of competent core is 14cm, rarely full diameter; Unknown metallic silver/tarnished black sulphide seen here associated with sphalerite; could be galena but not supershiny metallic as mentioned above	4	1		2	3			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B364874	6.71	7.62	**0.415**			VA05083121	0.91
5	1	2.0	4.5	40		2.0	q/cb	2	2	0.1			0.1					2.0				B364875	7.62	9.14	**0.084**			VA05083121	1.52
																						B364876	BLANK		**<0.005**			VA05083121	
4	1	1.0	4.0	60		4.0	q/cb	3	2	2.0								5.0				B364877	9.14	10.67	**0.729**			VA05083121	1.53
5	1	1.0	2.5	409		2.0	q/cb	2	2	1.0								5.0				B364878	10.67	12.19	**2.01**			VA05083121	1.52
3	1	1.5	3.0	50	35	4.0	q/cb	4	3								2.0					B364879	12.19	13.72	**0.378**			VA05083121	1.53
4	1	2.0	4.5	50		1.0	q/cb	4	4	1.0			0.1					5.0				B364880	13.72	15.24	**0.238**			VA05083121	1.52
6	1	3.0	7.0	30	45	2.0	q/cb	4	3	1.0								5.0				B364881	15.24	16.76	**2.21**			VA05083121	1.52
6	1	3.0	7.0	30	45	2.0	q/cb	4	3	1.0								5.0				B364882	15.24	16.76	**3.28**	DUP		VA05083121	1.52
2	1	1.0	2.0	50		8.0	cb/b	5	3						2.0							B364883	16.76	18.29	**0.033**			VA05083121	1.53
3	1	2.0	3.7	40		2.0	cb/q	4	2								0.1					B364884	18.29	19.81	**0.371**			VA05083121	1.52
4	1	1.5	4.0	50		1.0	q/cb	3	3	0.1								5.0				B364885	19.81	21.34	**0.338**			VA05083121	1.53
1	3	2.5	2.5	35		1.0	cb/q	2	3	1.0							2.0	5.0											
5	1	2.0	7.0	50		2.0	q/cb	3	4	2.0								5.0				B364886	21.34	22.86	**0.434**			VA05083121	1.52
5	1	1.0	4.5	40	20	1.0	q/cb	3	2	0.1								5.0				B364887	22.86	24.38	**3.42**			VA05083121	1.52
5	1	1.2	5.5	30	50	2.0	q/cb	3	3						1.0							B364888	24.38	25.71	**0.62**			VA05083121	1.33
5	1	1.2	5.5	30	50	2.0	q/cb	3	3						1.0							B364889	24.38	25.71	**0.76**	PD/CA		VA05083121	1.33
																						B364890	STANDARD 4D		**0.341**	4D		VA05083121	
6	1	1.0	4.0	60	35	1.0	q/cb	4	3	1.0					3.0			5.0				B364891	25.71	27.43	**0.624**			VA05083121	1.72
6	1	5.0	12.0	40		2.0	q/cb	3	3													B364892	27.43	28.96	**2.07**			VA05083121	1.53
6	1	3.0	8.0	60		2.0	q/cb	4	2	2.0								3.0				B364893	28.96	30.48	**0.165**		Broken core	VA05083121	1.52
3	1	1.0	3.0	60		3.0	q	3	3	1.0								3.0		1.0		B364894	30.48	32.00	**0.397**			VA05083121	1.52
0																						B364895	32.00	33.53	**0.657**			VA05083121	1.53
																						B364896	BLANK		**<0.005**			VA05083121	
3	1	1.5	3.5	50		1	q	2	2	1								5.0				B364897	33.53	35.05	**0.345**			VA05083121	1.52
3	1	1.0	3.0	50		3.0	q/cb	4	3													B364898	35.05	36.58	**0.069**			VA05083121	1.53
4	1	3.0	7.5	60		2.0	q/cb	4	4	0.1								5.0				B364899	36.58	38.10	**0.273**			VA05083121	1.52
6	1	1.0	5.0	30	60	8.0	q	4	4	1.0								5.0		3.0		B364900	38.10	39.62	**0.783**			VA05083121	1.52
3	1	1.5	3.5	45		2.0	q	3	3					1.0								B364901	39.62	41.15	**0.061**			VA05083121	1.53
3	1	1.5	3.5	45		2.0	q	3	3					1.0								B364902	39.62	41.15	**0.116**	DUP		VA05083121	1.53
4	1	2.0	8.0	45		2.0	q	3	4	0.1							3.0	5.0				B364903	41.15	42.67	**0.119**			VA05083121	1.52
0																						B364904	42.67	44.20	**0.218**			VA05083121	1.53
4	1	0.5	2.0	50		2.0	q/cb	4	4								1.0					B364905	44.20	45.72	**0.062**			VA05083121	1.52
5	1	2.0	5.2	45		2.0	q/cb	3	5	0.1							1.0	5.0				B364906	45.72	47.24	**0.803**			VA05083121	1.52
4	1	3.0	5.5	60		1.0	q/cb	3	5	0.1							1.0	5.0				B364907	47.24	48.77	**0.367**			VA05083121	1.53
3	1	2.0	4.0	65	4	q	4	2	0									5.0				B364908	48.77	50.29	**0.154**			VA05083121	1.52
3	1	2.0	4.0	65	4	q	4	2	0									5.0				B364909	48.77	50.29	**0.109**	PD/CA		VA05083121	1.52
																						B364910	STANDARD 7G		**4.42**	7G		VA05083121	
1	1	1.0	1.0	60		40.0	q/cb	5	5	0.1								5.0				B364911	50.29	51.82	**0.268**			VA05083121	1.53
1	4	0.2	0.2	50																							Same orange selvage		
3	1	1.0	3.0	45		2.0	q/cb	3	4	1.0								5.0				B364912	51.82	53.34	**0.593**			VA05083121	1.52
2	1	1.0	1.5	50		2.0	q/cb	2	4	1.0								5.0				B364913	53.34	54.86	**0.178**			VA05083121	1.52
2	1	1.0	2.0	60	45	1.0	q/cb	2	3	2.0								5.0				B364914	54.86	56.39	**0.076**			VA05083121	1.53
0																						B364915	56.39	57.91	**0.04**			VA05083121	1.52
																						B364916	BLANK		**0.683**			VA05083121	
5	1	3.0	7.0	40	60	3.0	q/cb	4	4						4.0		0.1					B364917	57.91	59.44	**0.469**			VA05083121	1.53
4	1	1.0	4.0	50		1.0	q/cb	5	4		5.0											B364918	59.44	60.21	**0.338**			VA05083121	0.77
3	1	1.5	4.0	40	60	6.0	q/cb	4	2		5.0		1.0									B364919	60.21	61.18	**0.073**			VA05083121	0.97
3	1	1.0	2.5	40		3.0	q/cb	3	4						5.0							B364920	61.18	62.48	**0.834**			VA05083121	1.30
1	1	1.0	1.0			1.0	q/cb	2	3													B364921	62.48	64.01	**0.197**			VA05083121	1.53
1	1	1.0	1.0			1.0	q/cb	2	3													B364922	62.48	64.01	**0.249**	DUP		VA05083121	1.53

DRILL HOLE # : DG05-307C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		86.87	110.50	GND: Slightly more competent GND but oxidation still pervasive; Carb-rich selvages reduced to fine sand texture over <5% of section; First 2m of section show moderate alteration in selvages and are quite competent (90%); Strong slickensides in carbonate/limonite on fracture faces at 40° TCA; @ 92.96m, a 40cm zone of sericite alteration occurs, with sericite. Carb influx and a loss of GND texture. A 0.2cm veinlet of oxidized iron product (hematite) may account for some of this alteration - a channel for hydrothermal waters. No slickensides but ductile shear is a possiblity here; From 96.01 - 97.54m fractures at 0° TCA break up rock which appears previously silicified and coarse-grained (up to 1cm grains of quartz and masses of biotite). @100.58m, clear large quartz veins with >5% sphalerite begin. Core is more competent here as well, to 107.25m; @ 103.63m, disseminated aspy seen covering ~5% of fracture face, no associated vein seen.	3	1	0	1	2	
10		110.50	117.35	GND: Oxidation much less prevalent but mineralogically and texturally altered with sericite, carbonate and chlorite; Evidence of shear and faulting: @ 111.45m, a fracture plane at 15° TCA has 2 sets of slickensides at 90° to one another (conjugate), expressed in bt, ser, chl, carb, hem (ox'd); On one side of this fracture, quartz veins appear while on the other side are none (plane of motion); Mineralization concentrated at margins of quartz veins, sometimes appearing as separate sulphide veins (at slightly different angles, possibly a later generation of the quartz veins); One set of slickensides @ 112.70m on fracture face at 30° TCA; From 115.82 - 117.2m influx of carbonate weakens rock along irregular fractures.	1	1	1	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2006

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
6	1	1.0	5.0	45		10.0	q/cb/s	5	4						1.0							B364923	64.01	65.53	**0.305**			VA05083121	1.52
2	3	0.2	0.4	55		1.0	q/cb	3	0		4.0																		
2	1	1.0	1.5	40	50	2.0	q/cb	4	4						5.0							B364924	65.53	67.06	**0.303**			VA05083121	1.53
2	1	0.5	1.0	50	0	2.0	q/cb	4	4						3.0							B364925	67.06	68.58	**0.044**			VA05083121	1.52
2	1	0.5	1.0			3.0	q	3	3						2.0							B364926	68.58	70.10	**0.058**			VA05082694	1.52
1	1	0.5	0.5	20		0.5	q	3	2													B364927	70.10	71.63	**0.065**			VA05082694	1.53
1	1	1.3	1.3	50		0.5	q/cb	4	1						0.1							B364928	71.63	73.15	**0.048**			VA05082694	1.52
1	1	1.3	1.3	50		0.5	q/cb	4	1						0.1							B364929	71.63	73.15	**0.062**	PD/CA		VA05082694	1.52
																						B364930	ANDARD 3C		**0.088**	3C		VA05082694	
1	1	1.0	1.0	50		8.0	cb	3	4										3.0	2.0		B364931	73.15	74.68	**0.131**			VA05082694	1.53
2	1	1.0	2.0	40		0.0			4	0.1								5.0				B364932	74.68	76.20	**0.133**			VA05082694	1.52
2	3	0.3	0.6	50	30	1.0	q/cb	3	1																				
2	1	2.0	3.0			4.0	q/cb	2	1	0.1								5.0				B364933	76.20	77.72	**0.176**		Pieces	VA05082694	1.52
8	1	1.0	5.5	50	130	1.0	q/cb	3	3						5.0		1.0	2.0				B364934	77.72	79.25	**0.229**			VA05082694	1.53
3	1	2.0	4.5	60		2.0	q/s	2	2	0.1					2.0			5.0				B364935	79.25	80.77	**0.269**			VA05082694	1.52
																						B364936	BLANK		**<0.005**			VA05082694	
4	1	1.5	4.0	60		2.0	q/cb/s	4	1								5.0					B364937	80.77	82.30	**0.13**			VA05082694	1.53
2	1	1.2	2.1	40		0.5	q/cb/s	3	2	0.1								5.0				B364938	82.30	83.82	**0.286**			VA05082694	1.52
2	1	1.0	2.0	30	50	0.0																B364939	83.82	85.34	**0.191**			VA05082694	1.52
2	1	1.5	2.0	50	70	2.0	q/s	2	3													B364940	85.34	86.87	**0.472**			VA05082694	1.53
4	1	2.0	4.2	30	50	2.0	q/cb/s	3	3						3.0							B364941	86.87	88.39	**0.114**			VA05082694	1.52
4	1	2.0	4.2	30	50	2.0	q/cb/s	3	3						3.0							B364942	86.87	88.39	**0.406**	DUP		VA05082694	1.52
3	1	1.0	2.4	45	0	8.0	q/s/cb	5	4	0.1								5.0				B364943	88.39	89.92	**1.245**			VA05082694	1.53
4	1	2.0	4.0	30	50	6.0	q	3	3	0.1					2.0			5.0				B364944	89.92	91.44	**0.054**			VA05082694	1.52
3	1	2.0	4.0	45	0	1.0	q/cb/s	3	3	0.1			0.1					4.0				B364945	91.44	92.96	**0.036**		Tiny fresh aspy	VA05082694	1.52
2	1	1.0	2.0	0		1.0	q	2	3													B364946	92.96	94.49	**0.065**			VA05082694	1.53
1	4	0.4	0.4	20		2.0	cb	3	2																				
3	1	1.5	3.0	30	40	1.0	q/cb/s	2	2													B364947	94.49	96.01	**0.212**			VA05082694	1.52
0																						B364948	96.01	97.54	**0.432**			VA05082694	1.53
0																						B364949	96.01	97.54	**0.551**	PD/CA		VA05082694	1.53
																						B364950	ANDARD 1A		**0.901**	1A		VA05082694	
2	3	1.0	2.0	40		1.0	cb/q	3	3				4.0						2.0	5.0		B364951	97.54	99.06	**0.493**			VA05082694	1.52
3	1	1.2	3.4	30	60	1.0	q/cb	3	3	1.0			2.0					5.0				B364952	99.06	100.58	**0.129**			VA05082694	1.52
3	1	2.0	4.0	45		2.0	q/cb	3	2	0.1			0.1		8.0							B364953	100.58	102.11	**0.555**			VA05082694	1.53
5	1	2.0	6.5	40	70	2.0	q/s/cb	3	4				1.0		5.0				2.0	3.0		B364954	102.11	103.63	**0.156**			VA05082694	1.52
4	1	2.0	5.0	60		10.0	q/cb	5	2				2.0		5.0					5.0		B364955	103.63	105.16	**0.507**			VA05082694	1.53
2	3	1.0	1.5	50	40	2.0	cb/q	3	3				0.1																
																						B364956	BLANK		**<0.005**			VA05082694	
3	1	1.5	3.5	55		1.5	q	3	2		2.0		0.1		1.0					1.0		B364957	105.16	106.68	**0.138**			VA05082694	1.52
3	1	1.0	1.6	45		1.0	q/cb	3	1		0.1				0.1					1.0		B364958	106.68	108.20	**0.34**			VA05082694	1.52
2	1	1.0	2.0	40		2.0	q	2	2						0.1							B364959	108.20	109.73	**0.092**			VA05082694	1.53
1	6	0.4	0.4	65		2.0	q/cb	4	2						10.0				40.0										
4	1	1.5	4.0	50		2.0	q/s/cb	3	3		0.1				0.1							B364960	109.73	110.50	**0.388**			VA05082694	0.77
6	1	1.0	4.5	50	35	18.0	s/chl	4	2	10.0	0.1		0.1		0.1							B364961	110.50	111.25	**0.466**			VA05082694	0.75
6	1	1.0	4.5	50	35	18.0	s/chl	4	2	10.0	0.1		0.1		0.1							B364962	110.50	111.25	**0.379**	DUP		VA05082694	0.75
5	1	2.0	6.0	50	35	20.0	s/cb/chl	5	2	10.0	2.0		10.0									B364963	111.25	112.03	**0.472**			VA05082694	0.78
5	1	2.0	5.0	50	25	2.0	q/cb	4	1		10.0		2.0		5.0				2.0			B364964	112.03	112.78	**0.324**			VA05082694	0.75
7	1	2.5	6.7	50		4.0	q/cb	3	2		5.0	0.1	1.0		0.1				2.0			B364965	112.78	114.30	**0.092**			VA05082694	1.52
4	3	1.5	4.0	50		2	q/cb/s	4	1				6.0																
5	1	2.5	6.0	25	50	2.0	q/cb	4	1		10.0	2.0	1.0									B364966	114.30	115.82	**0.133**			VA05082694	1.52

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 5 of 14		
DRILL HOLE # : DG05-307C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.35	128.02	GND: Unaltered GND with mineralized, frequent quartz veins; Sphalerite continues, as well as massive po with a relatively large amount of cpy. Aspy appears irregularly (locally up to 10%, and association with quartz vein - may be later); Large vein @ 119.90m contains well-formed, shiny large biotite within vein.	1	1	1	0	1	
10		128.02	134.11	GND: Increase in carbonate with limonite along 30° and 130° fract, plus at irregular angles; Weakens and breaks rocks into <1cm pieces in 3 zones; Longest competent core is 15cm; 75% unaltered GND - alteration occurs in small selvages surrounding quartz veins, carbonate veinlets and the last sample of the interval is gradation into sericite-rich zone.	2	2	0	1	2	
10		134.11	138.27	GND: Zone of extreme alteration: sericitized, predominantly, plus moderate carbonitization; Only quartz eyes left of GND texture and overall colour is dark bluish green; Limonite on most fracture faces with some infiltration (selvages up to 1cm) into surrounding rock; 'Veins' noted are not solid or straight - only chunks of quartz in a line: chunks are rounded and have sulphides (partially oxidized py) within interstices of quartz.	2	5	2	0	2	
10		138.27	142.71	GND: Still highly altered, but with more carbonate, in anhedral to subhedral laths up to 3cm long and 0.5cm wide, within lighter blue-green matrix than previous section.	1	5	1	1	3	
10		142.71	147.83	GND: Approx 50% unaltered, unoxidized GND; Wide (10cm) oxidation selvages around cracks/veinlets of limonite; Quartz veins and sulphide veins have selvages as well, and irregular veinlets of limonite continue through section; Massive pyrite associated with >2cm quartz veins is linearly distributed through vein as well as 10cm of vein, in same orientation.	2	2	0	0	2	
10		147.83	153.16	GND: Wide selvages around qtz and sulphide veins dominate section; Med grained unaltered GND.	1	3	0	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval					
						Selvages				Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	ascordite	biotite	other		From	To					
2	1	1.0	2.0	20	50	2.0	q/s/cb	2	0		2.0								3.0			B364967	115.82	117.35	**0.103**			VA05082694	1.53
8	1	1.0	8.0	50	40	1.0	q/cb	3	1		5.0	1.0	1.0		2.0							B364968	117.35	118.87	**0.367**			VA05082694	1.52
8	1	1.0	8.0	50	40	1.0	q/cb	3	1		5.0	1.0	1.0		2.0							B364969	117.35	118.87	**0.101**	PD/CA		VA05082694	1.52
																						B364970	ANDARD 5E		**1.386**	5E		VA05082694	
5	1	1.5	4.5	50	65	4.0	q	3	1		2.0								2.0			B364971	118.87	120.40	**0.044**			VA05082694	1.53
3	1	6.0	8.0	45		3.0	q/s/cb	3	1		8.0	1.0	5.0		2.0				3.0	10.0		B364972	120.40	120.98	**0.216**			VA05082694	0.58
1	3	0.4	0.4	45		1.0	q/cb	4	0		0.1																		
5	1	15.0	18.0	40	50	0.5	q/s/cb	2	0	1.0	5.0		2.0		6.0				1.0			B364973	120.98	121.92	**5.99**			VA05082694	0.94
4	1	3.0	7.0	45		2.0	q/s/cb	4	0		6.0		4.0						1.0	1.0		B364974	121.92	123.44	**0.327**			VA05082694	1.52
9	1	2.0	9.0	40	50	2.0	q/cb	2	0		8.0		2.0									B364975	123.44	124.97	**0.112**			VA05082694	1.53
																						B364976	BLANK		**<0.005**			VA05082694	
6	1	1.5	5.5	40	50	2.0	q	0		3.0										4.0		B364977	124.97	126.49	**0.313**			VA05082694	1.52
3	1	1.0	3.0	30		1.0	q	3	0		3.0									1.0		B364978	126.49	128.02	**0.063**			VA05082694	1.53
4	1	0.5	2.0	50		1.0	q/cb	3	0		2.0		0.1						1.0	1.0		B364979	128.02	129.54	**0.211**			VA05082694	1.52
5	1	0.5	2.5	50		1.0	q	2	2		4.0		0.1						2.0			B364980	129.54	131.06	**0.222**			VA05082694	1.52
2	1	1.5	2.0												0.1							B364981	131.06	132.59	**0.668**		Broken core	VA05082694	1.53
2	1	1.5	2.0												0.1							B364982	131.06	132.59	**0.781**	DUP		VA05082694	1.53
2	1	3.0	4.0	40		0.5	q/cb	3	1	2.0			0.1					4.0				B364983	132.59	134.11	**0.23**			VA05082694	1.52
1	1	4.0	4.0	30		0.0				10.0								1.0				B364984	134.11	135.64	**0.274**			VA05082694	1.53
2	1	1.0	2.0	10		0.0				2.0												B364985	135.64	137.16	**0.068**			VA05082694	1.52
3	1	1.0	3.0	30		0.0				2.0												B364986	137.16	138.27	**0.346**			VA05082694	1.11
1	6	4.0	4.0	40						100.0								5.0				B364987	138.27	139.16	**0.34**		All alt'd, all py ox'd	VA05082694	0.89
5	1	5.0	9.0	60	110					1.0												B364988	139.16	140.21	**0.094**			VA05082694	1.05
5	1	5.0	9.0	60	110					1.0												B364989	139.16	140.21	**0.106**	PD/CA		VA05082694	1.05
																						B364990	ANDARD 7G		**4.64**	7G		VA05082694	
5	1	1.0	5.0	40	20					5.0								2.0				B364991	140.21	141.73	**0.133**			VA05082694	1.52
1	6	10.0	10.0	60						100.0								4.0											
0																						B364992	141.73	142.71	**0.059**			VA05082694	0.98
0																						B364993	142.71	143.26	**0.047**			VA05082694	0.55
8	1	1.0	8.0	60		2.0	q/s/cb	5	3	1.0	6.0		2.0		1.0			4.0				B364994	143.26	144.78	**0.561**			VA05082694	1.52
4	1	1.5	4.0	70		8.0	s/cb	4	3	4.0			2.0									B364995	144.78	146.30	**0.492**			VA05082694	1.52
1	6	2.0	2.0	70		30.0	s/cb	5	1	95.0								2.0											
																						B364996	BLANK		**<0.005**			VA05082694	
7	1	1.0	2.8	60		4.0	q/s	4	1	10.0	3.0							1.0				B364997	146.30	147.83	**0.366**			VA05082694	1.53
2	1	3.0	5.0	50		30.0	s	4	1	12.0	2.0		0.1									B364998	147.83	149.35	**0.149**		Massive py	VA05082694	1.52
4	1	1.0	4.0	50		4.0	5	4	1	10.0	5.0		0.1									B364999	149.35	150.03	**0.292**			VA05082694	0.68
2	6	1.0	2.0	60		20.0	cb/s	5		70.0																			
3	1	1.0	2.5	60																		B365000	150.03	150.88	**0.134**		Selvage not distinct from alt'n	VA05082694	0.85
1	4	0.3	0.3	40		15	cb/s	5	2	20								4.0											
2	1	2.0	3.0	50	130	10.0	s	5		5.0	0.1							2.0				B365001	150.88	151.64	**1.98**			VA05082694	0.76
2	6	4.0	4.0	130		30.0	s/cb	5	1	60.0								1.0											
2	1	2.0	3.0	50	130	10.0	s	5		5.0	0.1							2.0				B365002	150.88	151.64	**1.32**	DUP		VA05082694	0.76
2	6	4.0	4.0	130		30.0	s/cb	5	1	60.0								1.0											
4	1	1.0	3.0	45	60	15.0	s/q	5	0	3.0	2.0		2.0					1.0				B365003	151.64	152.40	**0.062**			VA05082694	0.76
1	3	0.3	0.3	30		2.0	q/cb/k	4	1		0.1									3.0									
6	1	2.0	6.0	50	60	2.0	s/cb/q	3	1		4.0		2.0									B365004	152.40	153.16	**0.363**			VA05082694	0.76
2	3	0.3	0.6	70		6.0	cb/s	5		30.0	6.0							3.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 7 of 14		
DRILL HOLE # : **DG05-307C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		153.16	161.54	GND: Moderately to highly altered GND, surrounding numerous quartz and sulphide veins; Slickensides (weak to moderate) are seen throughout section, expressed in sericite + carbonate. Also motion along fractures-quartz veins truncated, and irregular in width and orientation; Because alteration is so pervasive in some areas (on 1-2m scale), selvage widths are difficult to distinguish, especially where veins are numerous; Pyrite in veins is predominantly fresh (not oxidized), but when associated with carbonate it is virtually all oxidized and clay rich; Regular fracturing @ 30 - 60° (variable across section, ~8 per m, straight).	1	4	1	1	3	
10		161.54	182.04	GND: Poor recovery. Rock is soft (sericite and carbonate altered) and is very broken up from 161.54 - 168.8m. Followed by very hard, silicified GND with little to no carbonate alteration, from 169.0 - 170.35m; Sericite still affecting this section, appears previous to silicification; Rock grades between two extremes (varying amounts of late carbonate) for whole section; Pyrrhotite appears 'fused' (black magnetic mass with the occasional fresh po within).	0	3	0	1	1	
10		182.04	183.44	GND: Weak, quartz-rich section of GND; Weakened by intense sericitization and carbonatization; Low specific gravity; Colour is white.		4		2	4	
10		183.44	213.60	GND: Moderately carb-altered God with sericitized selvages around medium to large (2-3cm) quartz veins (~2 per m) with mineralization; @ 192.5m, a 5cm zone with sharp boundaries at 15° TCA, appears to be sheared into position. These clues continue to end of section.	0	3	1	1	3	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
8	1	1.0	6.0	60			s/cb	4		5.0	1.0		0.1					4.0				B365005	153.16	153.92	**0.339**			VA05082694	0.76
2	1	3.0	4.0	75						5.0								4.0				B365006	153.92	154.72	**0.532**			VA05082694	0.80
2	6	1.0	2.0	75		4.0	cb/s	5	1	100.0								4.0											
6	1	1.0	6.0	70	50	2.0	q/s	3	0		8.0	0.1										B365007	154.72	155.45	**0.368**			VA05082694	0.73
6	1	2.0	6.0	50		2.0	q	3	1	0.1	3.0							5.0				B365008	155.45	156.97	**0.123**			VA05082694	1.52
6	1	2.0	6.0	50		2.0	q	3	1	0.1	3.0							5.0				B365009	155.45	156.97	**0.126**	PD/CA		VA05082694	1.52
																						B365010	ANDARD 6F		**2.91**	6F		VA05082694	
5	1	1.5	3.5	50		1.0	q	3	0	0.0		3.0										B365011	156.97	158.50	**0.067**			VA05082694	1.53
8	1	2.0	9.5	50		2.0	q/s/cb	3	1	1.0	5.0		0.1									B365012	158.50	160.02	**0.267**			VA05082694	1.52
5	1	2.0	5.0	70	40	4.0	q/cb/s	4			5.0									1.0		B365013	160.02	160.71	**0.833**		Py all oxidized	VA05082694	0.69
1	6	1.0	1.0	60		20.0	s	4		60.0								5.0											
4	1	2.0	7.0	30	75					2.0	5.0		0.1					4.0				B365014	160.71	161.54	**0.041**		All altered	VA05082694	0.83
1	1	11.0	11.0	60	150	70.0	cb	3	0	4.0								5.0				B365015	161.54	163.02	**0.626**			VA05082694	1.48
																						B365016	BLANK		**<0.005**			VA05082694	
2	1	1.0	1.5	50		1.0	q	3	0	1.0	4.0							3.0				B365017	163.02	164.59	**0.22**			VA05082694	1.57
4	1	1.0	4.0	60		0.0				0.1					0.1							B365018	164.59	166.12	**0.445**		Trace Sphalerite?	VA05082694	1.53
1	3	1.0	1.0	60		1.0	q	2											0.1			B365019	166.12	167.64	**0.033**			VA05082694	1.52
4	1	1.0	4.0	50		2.0	q/cb	2														B365020	167.64	169.16	**0.11**		Sulph clay	VA05082694	1.52
1	6	8.0	8.0	70			cb	3										100.0											
5	1	1.0	4.5	40		1.0	q	2														B365021	169.16	170.69	**0.054**			VA05082694	1.53
5	1	1.0	4.5	40		1.0	q	2														B365022	169.16	170.69	**0.792**	DUP		VA05082694	1.53
1	1	1.0	1.0			1.0	q	3										0.1				B365023	170.69	172.21	**0.027**		Very broken	VA05082694	1.52
1	1	1.5	1.5	70		1.0	q	2			3.0										2.0	B365024	172.21	173.74	**0.031**		Oxidized po?	VA05082694	1.53
2	3	0.3	0.6	60		2.0	q/s	3			5.0										1.0	B365025	173.74	175.26	**0.036**			VA05082694	1.52
3	1	2.0	4.0	40		4.0	q/s	3			10.0	2.0										B365026	175.26	176.78	**0.026**			VA05082695	1.52
5	1	4.0	8.5	20	40	1.0	q	2			2.0											B365027	176.78	178.31	**0.117**			VA05082695	1.53
2	1	1.0	2.0	50		1.0	q	2			5.0									1.0	2.0	B365028	178.31	179.83	**0.03**			VA05082695	1.52
2	1	1.0	2.0	50		1.0	q	2			5.0									1.0	2.0	B365029	178.31	179.83	**0.042**	PD/CA		VA05082695	1.52
																						B365030	ANDARD 2B		**3.06**	2B		VA05082695	
5	1	1.0	5.0	50		1.0	q	2			3.0									1.0		B365031	179.83	181.36	**0.057**			VA05082695	1.53
2	1	1.0	2.0	30		4.0	q/s	4												0.1		B365032	181.36	182.04	**0.067**			VA05082695	0.68
																						B365033	182.04	182.88	**0.513**			VA05082695	0.84
																						B365034	182.88	183.44	**0.046**			VA05082695	0.56
2	1	1.0	2.0	40		2.0	q/s	3	1		2.0										1.0	B365035	183.44	184.40	**0.106**			VA05082695	0.96
2	6	0.5	1.5	25		1.0	cb	5		6.0											2.0								
																						B365036	BLANK		**<0.005**			VA05082695	
5	1	1.0	4.5	60	40	3.0	q/s	4	0		1.0									4.0		B365037	184.40	185.93	**1.065**			VA05082695	1.53
5	1	2.0	4.0	50		1.0	q/s	4			6.0											B365038	185.93	187.45	**0.133**			VA05082695	1.52
4	1	10.0	15.5			15	s/chl	4	0	3.0		1.0										B365039	187.45	188.98	**0.526**			VA05082695	1.53
2	1	8.0	11.0	10		1.0	q/cb	2	0		2.0											B365040	188.98	190.50	**0.132**			VA05082695	1.52
2	1	3.0	4.0	35		2.0	q/3	3														B365041	190.50	192.02	**0.037**			VA05082695	1.52
1	6	0.5	0.8	35		10.0	cb	2										100.0											
2	1	3.0	4.0	35		2.0	q/3	3														B365042	190.50	192.02	**0.121**	DUP		VA05082695	1.52
1	6	0.5	0.8	35		10.0	cb	2										100.0											
2	1	1.0	2.0	50		6.0	q/s	3		3.0								1.0				B365043	192.02	193.50	**0.11**		Black clay beside quartz vein (carb-rich)	VA05082695	1.48
1	3	5.0	5.0	15		0.0																							
5	1	1.0	4.5	50	30	8.0	q/s	5			8.0							2.0				B365044	193.50	195.07	**0.166**			VA05082695	1.57
5	1	1.3	5.8	40		6.0	q/s	3			4.0							1.0				B365045	195.07	196.60	**0.343**			VA05082695	1.53
4	1	2.0	5.5	10		1.0	q	2			5.0									5.0		B365046	196.60	198.12	**0.076**			VA05082695	1.52
6	1	2.0	5.5	30	60	1.0	q	3		0.1	0.1							2.0				B365047	198.12	199.64	**0.064**			VA05082695	1.52
2	1	1.0	2.0	45		4.0	q/s	2			4.0											B365048	199.64	201.17	**0.39**			VA05082695	1.53
1	6	0.4	0.4	40		30.0	5	4		80.0								10.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 9 of 14		
DRILL HOLE # : **DG05-307C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		213.51	217.00	GND: Limonite appears again on fracture faces; GND competent with regular fracturing at 60° TCA.	1	1	0	0	1	
10		217.00	217.93	GND: Highly altered section; GND texture reduced to quartz eyes within sericitized/carbonate altered matrix; 2 to 3 quartz veins still visible with no distinguishable selvages; One quartz vein has ~60% oxidized pyrite, clay rich.	1	4	1	2	2	
10		217.93	225.55	GND with numerous medium-sized quartz veins; Late carbonate alteration moderate; Weak, broken up to crumbly rock.	0	2	0	1	3	
10		225.55	245.36	GND: Weak, crumbly carbonate-rich GND: Other than late carbonate, GND is unaltered except from 230.4 - 230.55m with a wide selvage around carb/oxidized pyrite clay vein-sericitized; Slickensides expressed in sericite and carbonate on fracture face @ 50° TCA; Sericite/carbonate for 10cm @ 241.4m surrounding quartz/carb vein; Increased sulphide content in veins is associated with larger selvages especially (oxidized) pyrite.	0	1	0	1	3	
10		245.36	254.51	GND: Competent core except in a few sericite-altered zones, from 246 - 246.7 (surrounding sulphide-rich quartz veins) and from 247.0 - 247.4m (same) and 247.8 - 248.0m, and 250.5 - 250.6m; These sericite zones are more crumbly than unaltered GND in between; Quartz veins toward the end of the section show decreased mineralization; The last 50cm is gradational to the next section.	0	2	0	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides										Oxidation					Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
2	1	1.0	2.0	45		4.0	q/s	2			4.0											B365049	199.64	201.17	**0.327**	PD/CA		VA05082695	1.53
1	6	0.4	0.4	40		30.0	5	4		80.0								10.0											
																						B365050	ANDARD 5E		**1.44**	5E		VA05082695	
1	1	1.0	1.0	50		10.0	s/cb	4			10.0	1.0							6.0			B365051	201.17	202.69	**0.099**			VA05082695	1.52
4	1	2.0	5.5	50		2.0	q/s	2		0.1	0.1											B365052	202.69	204.22	**0.172**			VA05082695	1.53
6	1	2.0	6.5	30	70	2.0	s/q	3			2.0								3.0			B365053	204.22	205.74	**0.102**			VA05082695	1.52
1	1	1.5	1.5	25	165	2.0	q/s	2			4.0							1.0				B365054	205.74	207.26	**0.615**			VA05082695	1.52
5	1	2.0	5.5	50	30	8.0	s	4			6.0							2.0				B365055	207.26	208.79	**0.063**			VA05082695	1.53
																						B365056	BLANK		**<0.005**			VA05082695	
3	1	1.0	3.3	3	55	0.5	q	2			2.0											B365057	208.79	210.31	**0.088**			VA05082695	1.52
5	1	1.5	5.5	60	30	1.0	q	3			1.0							1.0				B365058	210.31	211.84	**0.41**			VA05082695	1.53
2	1	0.4	0.8	60		2.0	q/s	3			1.0							1.0				B365059	211.84	212.59	**0.042**			VA05082695	0.75
2	1	1.0	2.0	40		1.0	q	3			1.0							1.0				B365060	212.59	213.51	**0.078**			VA05082695	0.92
1	1	1.0	1.0	45		1.0	q/s	3			2.0								4.0			B365061	213.51	214.88	**0.117**			VA05082695	1.37
1	1	1.0	1.0	45		1.0	q/s	3			2.0								4.0			B365062	213.51	214.88	**0.056**	DUP		VA05082695	1.37
4	1	1.0	4.0	50		4.0	q/s	3			2.0									2.0		B365063	214.88	216.41	**0.085**			VA05082695	1.53
3	1	1.0	3.0	40		4.0	q/cb/s	4			0.1								2.0	2.0		B365064	216.41	216.81	**0.461**			VA05082695	0.40
2	1	1.0	2.0	40		6.0	q/s	3												0.1		B365065	216.81	217.93	**0.124**			VA05082695	1.12
1	6	1.0	1.0	70			s	5										60.0											
3	1	1.0	3.0	60		2.0	q/s	4			1.0									2.0		B365066	217.93	219.46	**0.042**		Oxidized py clay	VA05082695	1.53
3	1	1.0	3.0	65		2.0	q/s	2			3.0									1.0		B365067	219.46	220.98	**0.05**			VA05082695	1.52
4	1	1.0	4.0	45		2.0	q/cb/s	4			1.0										1.0	B365068	220.98	222.50	**0.152**			VA05082695	1.52
4	1	1.0	4.0	45		2.0	q/cb/s	4			1.0										1.0	B365069	220.98	222.50	**0.13**	PD/CA		VA05082695	1.52
																						B365070	ANDARD 6F		**2.94**	6F		VA05082695	
4	1	1.3	4.0	60	30	2.0	q/cb	3			5.0								1.0	2.0		B365071	222.50	224.03	**0.43**			VA05082695	1.53
5	1	1.5	5.5	50	10	2.0	q/cb	5			6.0	0.1						2.0		2.0		B365072	224.03	225.55	**0.488**			VA05082695	1.52
3	1	1.0	2.5	60		2.0	q/s	3			1.0							1.0				B365073	225.55	227.08	**0.298**			VA05082695	1.53
4	1	1.0	4.0	60		1.0	q/cb	2			4.0									2.0		B365074	227.08	228.60	**0.074**			VA05082695	1.52
3	1	1.0	3.0	50	30	1.0	q/cb	4			7.0							1.0		2.0		B365075	228.60	231.12	**1.13**			VA05082695	2.52
2	3	1.5	2.0	45		2.0	q	2			0.1								1.0										
																						B365076	BLANK		**<0.005**			VA05082695	
2	1	2.0	3.0	40	70	2.0	q/s	2			2.0									1.0		B365077	230.12	231.65	**0.148**			VA05082695	1.53
1	4	1.0	1.0	70		25.0	cb/s	5										40.0											
5	1	1.2	4.5	45		1.0	q/cb	4			3.0									2.0		B365078	231.65	233.17	**0.551**			VA05082695	1.52
4	1	1.5	4.0	60		2.0	q/cb/s	4			5.0										4.0	B365079	233.17	234.70	**1.575**			VA05082695	1.53
3	1	1.4	3.4	20	50	2.0	q/s	3			5.0											B365080	234.70	236.22	**0.091**			VA05082695	1.52
2	3	0.5	0.8	40		10.0	cb/s	4										10.0											
4	1	1.0	4.0	60		1.0	q/s	3			0.1								5.0	2.0		B365081	236.22	237.74	**0.704**			VA05082695	1.52
4	1	1.0	4.0	60		1.0	q/s	3			0.1								5.0	2.0		B365082	236.22	237.74	**0.694**	DUP		VA05082695	1.52
3	1	0.8	2.4			1.0	q/s	1	0		1.0											B365083	237.74	239.87	**0.053**			VA05082695	2.13
5	1	1.0	4.0	50	60	3.0	q/s	3		0.1	2.0								2.0			B365084	239.87	240.79	**0.082**			VA05082695	0.92
5	1	1.2	6.0	40		1.0	q	1			0.1									2.0		B365085	240.79	242.32	**0.213**			VA05082695	1.53
1	3	1.2	1.2	80		10.0	s/cb	4																					
4	1	1.0	4.0	60	40	2.0	q/s	2			1.0								5.0	0.1		B365086	242.32	243.84	**0.028**			VA05082695	1.52
4	1	1.0	4.0	55		1.0	q	4			2.0											B365087	243.84	245.36	**0.049**			VA05082695	1.52
5	1	1.0	4.5	60		30.0	s/cb	4		6.0	3.0							1.0		3.0	1.0	B365088	245.36	246.89	**0.368**			VA05082695	1.53
5	1	1.0	4.5	60		30.0	s/cb	4		6.0	3.0							1.0		3.0	1.0	B365089	245.36	246.89	**0.548**	PD/CA		VA05082695	1.53
																						B365090	ANDARD 4D		**0.447**	4D		VA05082695	
2	1	4.0	4.5	70		6.0	s/cb	5	2	5.0	10.0							10.0				B365091	246.89	248.41	**0.145**			VA05082695	1.52
1	6	0.5	0.5	60		50.0	s/chl	4	0	5.0								65.0											
4	1	1.0	3.0	35	55	2.0	q	3			1.0											B365092	248.41	249.94	**0.045**			VA05082695	1.53
3	1	0.8	1.5	70		1.0	q/cb	2			1.0							1.0				B365093	249.94	251.46	**0.077**			VA05082695	1.52
6	1	1.0	4.0	65		2.0	q/s	2			1.0							1.0				B365094	251.46	252.98	**0.109**			VA05082695	1.52
5	1	2.0	4.5	50		2.0	q/s	2		0.1	0.1											B365095	252.98	254.51	**0.076**			VA05082695	1.53
																						B365096	BLANK		**<0.005**			VA05082695	

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 11 of 14		
DRILL HOLE # : **DG05-307C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		254.51	263.65	GND: Pervasively sericitized GND; Crumbly and clay-rich. Also carbonate-rich; Quartz eyes remain; Shear evidence in 'smeared' oxidized pyrite veinlets and quartz veins moved 1-2cm dextrally at 50° TCA; Selvages removed/not visible in altered matrix; Quartz veins only partial within altered matrix, often been sheared away; Carbonate veinlets and sulphide veins at 70-80° TCA.	1	5	0	3	3	
10		263.65	284.29	GND: Carbonate and sericite alteration still strong, but separated by medium to dark grey unaltered GND; Carbonate alteration more effective here, even unaltered GND is infused with it for 1-2m in bottom half of section (late carb); Colour of altered zones is more pale beige (early) than the blue-green of the last section (early = competent, late = crumbly); Section is 80% competent rock; Section is 10% unaltered GND to 277.37 and then 40% unaltered from 277.37 284.29m; Late carbonate effects both altered and unaltered GND throughout section; Alteration is not always attrubuted to veining, often no vein visible whre pervasive sericite/carbonate alteration appears; Slickensides visible on most fracture faces at 45° TCA; 'Bleached' section from 283.0m to 284.1m where color is yellowish white, contacts unaltered GND (upper) at 20° TCA; May be considered selvage around low-angle quartz veins and one high angle sulphide vein. Silicified.	1	4	1	2	4	
10		284.29	286.51	GND: Competent core; Unaltered with quartz veins to 285.5m, where fracture at 0-5° TCA (parallel for 1m) denotes shear zone boundary; Half of core is still unaltered with quartz veins (altered selvages) while half is totally carbonate and sericite infused and texture sheared through with carbonate and oxidized sulphide clays.	0	2	1	1	3	
10		286.51	288.39	GND: Sheared material now makes up entire core, apparent shear direction is @ 50° TCA; 70% of section is soft, clay-rich crumbly, carb-rich, sericitic gravel (quartz eyes) to clay texture. Veins seen in competent bits (pieces no longer than ~12cm). Contact with competent next section is at 55° TCA.	1	4	1	3	4	
10		288.39	291.08	GND: Unaltered GND between selvages surrounding quartz and carbonate veins with minimal mineralization.	0	2	0	0	3	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	0.5	2.0	70	50					0.1								4.0				B365097	254.51	256.03	**0.14**		All Altered	VA05082695	1.52
2	1	1.0	1.5	50						0.1								1.0				B365098	256.03	257.56	**0.694**			VA05082695	1.53
2	1	1.0	1.6	50	30	0.0				0.1								3.0				B365099	257.56	259.08	**0.024**			VA05082695	1.52
3	1	0.5	1.5	30	80					8.0								2.0				B365100	259.08	260.60	**0.469**			VA05082695	1.52
3	6	2.0	5.0	70						70.0								30.0											
4	1	1.2	3.5	60	80	1.6	cb/s	5										5.0				B365101	260.60	262.13	**0.017**			VA05082695	1.53
2	4	0.5	1.0	80	110																								
4	1	1.2	3.5	60	80	1.6	cb/s	5										5.0				B365102	260.60	262.13	**0.019**	DUP		VA05082695	1.53
2	4	0.5	1.0	80	110																								
4	1	0.5	2.0	60	20					8.0								10.0				B365103	262.13	263.65	**0.24**			VA05082695	1.52
1	3	1.0	1.0	50														10.0											
3	6	2.0	4.5	60	140					70.0								30.0											
4	1	2.0	5.0	40	60	2.0	s/q	3		0.1	3.0							1.0				B365104	263.65	265.18	**0.057**			VA05082695	1.53
1	6	0.3	0.3	60		6.0	s/cb	4										90.0											
3	1	1.2	4.4	70		10.0	q/cb	4			0.1							2.0				B365105	265.18	266.70	**0.068**			VA05082695	1.52
7	1	1.0	4.5	65	40	10.0	cb/s	4			3.0							0.1				B365106	266.70	268.22	**0.161**			VA05082695	1.52
1	1	0.4	0.4	55		1.0	cb/s	4										0.1				B365107	268.22	269.75	**0.236**			VA05082695	1.53
2	6	0.4	0.8	45		6.0	cb/s	5		40.0								40.0											
5	1	1.0	3.6	60	70	1.0	cb	5		5.0								0.1				B365108	269.75	271.27	**0.184**		5% py in one vein only	VA05082695	1.52
2	3	4.0	5.0	60	70	20.0												10.0											
5	1	1.0	3.6	60	70	1.0	cb	5		5.0								0.1				B365109	269.75	271.27	**0.197**	PD/CA		VA05082695	1.52
2	3	4.0	5.0	60	70	20.0												10.0											
																						B365110	ANDARD 1A		**0.848**	1A	Po and py in different veins	VA05082695	
4	1	0.5	2.0	60		4.0	q/cb	4		4.0	7.0							2.0				B365111	271.27	272.80	**0.695**			VA05082695	1.53
1	1	1.0	1.0	60		0.5	cb	5		3.0								0.1				B365112	272.80	274.32	**0.037**			VA05082695	1.52
4	1	1.0	2.4	35		1.0	cb	4										0.1				B365113	274.32	275.84	**0.118**			VA05082695	1.52
3	3	1.0	2.2	30	70					5.0								1.0											
2	6	1.0	2.0	60		2.0	q/cb	4		30.0								40.0											
8	1	1.0	6.0	70	50	1.0	cb	4										2.0				B365114	275.84	277.34	**0.066**			VA05082695	1.50
2	3	1.5	2.9	115														10.0											
2	6	0.3	0.6	130						10.0								50.0											
9	1	1.0	6.5	40	70	2.0	q/cb	4		5.0								5.0				B365115	277.34	278.89	**0.31**			VA05082695	1.55
1	4	0.5	0.5	70		10.0	cb/s	4																					
																						B365116	BLANK		**<0.005**			VA05082695	
3	1	1.0	3.0	70	50	2.0	cb/q	4			1.0							5.0				B365117	278.89	280.42	**0.653**			VA05082695	1.53
1	6	0.4	0.4	140		10.0	cb/s	5	1	5.0								80.0											
5	1	1.0	4.0	40	60	2.0	q/cb	4			2.0							4.0				B365118	280.42	281.94	**0.143**			VA05082695	1.52
4	1	1.0	2.0	20		1.0	q/cb	4										2.0				B365119	281.94	283.46	**0.734**			VA05082695	1.52
2	6	0.2	0.4	30	40	20.0	cb/s	4		20.0								60.0											
2	1	1.0	1.5	30	50													2.0				B365120	283.46	284.29	**0.857**			VA05082695	0.83
1	6	1.0	1.0	85														60.0											
5	1	2.0	5.5	40		2.0	q/s	3			6.0								2.0			B365121	284.29	284.99	**0.728**			VA05082695	0.70
5	1	2.0	5.5	40		2.0	q/s	3			6.0								2.0			B365122	284.29	284.99	**0.363**	DUP		VA05082695	0.70
7	1	1.5	7.0	50		4.0	q/s/cb	4			5.0							1.0		0.1		B365123	284.99	286.51	**0.343**			VA05082695	1.52
1	1	1.5	1.5	35		2.0	q/s	2			0.1							0.1		0.1		B365124	286.51	287.53	**0.119**			VA05082695	1.02
2	6	1.0	2.0	50														80.0											
4	1	0.5	2.0	70		1.0	q/s	2			0.1											B365125	287.53	288.39	**0.296**			VA05082695	0.86
3	1	1.2	2.6	50		2.0	cb/s	3			2.0							0.1		0.1		B365126	288.39	289.56	**0.112**			VA05082695	1.17
2	4	0.6	1.0	70		10.0	cb/s	4										4.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 13 of 14		
DRILL HOLE # : DG05-307C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.0	2.3	60		6.0	cb/s	4			3.0											B365127	289.56	291.08	**0.035**			VA05082695	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-308C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1115m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 24 - Sept. 1, 2005

DATES LOGGING: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459956 NORTHING: 7099086

COORD SYSTEM: NAD 83: EASTING: 459837 NORTHING: 7099271

NAD 27 (CORRECTED for historic grid): EASTING: 459926 NORTHING: 7099096

SECTION LINE(historic grid)

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 6.10 m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B365548 - B365697

Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05

Lab Record #: VA05083821 Date Received: 28-Sept-05

Sample Sequence: B365698 - B365794

Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05

Lab Record #: VA05083822 Date Received: 28-Sept-05

Duplicates:	B365562, B365582, B365602, B365622, B365642, B365662, B365682, B365702, B365722, B365742, B365762, B365782
Preparation Duplicate/ Check Assay:	B365549, B365569, B365589, B365609, B365629, B365649, B365669, B365689, B365709, B365729, B365749, B365769, B365789
Standards:	B365550 (1A), B365570 (3C), B365590 (4D), B365610 (5E), B365630 (1A), B365650 (6F), B365670 (3C), B365690 (7G), B365710 (2B), B365730 (5E), B365750 (4D), B365770 (3C), B365790 (2B)
Blanks:	B365556, B365576, B365596, B365616, B365636, B365656, B365676, B365696, B36555716, B365736, B365756, B365776

FROM	TO	LITHOLOGY
0.00	6.10	CASING
6.10	27.43	MSED
27.43	34.30	HFLS
34.30	299.31	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
54.9	331.7	48.2	357.7	358.7
115.8	332.1	49.7	358.1	359.1
207.3	333.0	48.0	359.0	360.0
298.7	332.2	44.3	358.2	359.2

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 1 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
1	0-6.10	0.00	6.10	Casing. No recovery.						
80	6.10-27.43	6.10	27.43	MSED are very broken up and frac'd with poor recovery. Frac faces are lim with mnr cb. MSED's interchange between silicified bio and grey qtz fol'd MSED and non-silicified dark bio-rich, soft, white, randomly orientated, euhedral laths. QV's are common but with no fresh mineralization observed (2% ox'd vugs). Interval 7.62-9.14m is one broken up qv (sampled B365548). Silicified core is more abundant. Fresh bio blebs occur locally in bio-rich, soft core. Foliations: 9.44m at 30°, 11.90m at 45°, 13.40m at 60°, 14.50m at 50°, 15.54m at 60°, 18.00m at 60°, 24.20m at 45°.	2					
81	27.43-34.30	27.43	34.30	MSED; HFLS is heavily frac'd and much more lim than previous interval. Core is dark, soft, bio-rich and very fine grained and foliated. Qv's x-cutting fol'n have fingered into the fol'ns. Very fine grained soft white minerals speckled through out. Contact with GND is between 33.53 and 35.05 (crumbled sub-rounded core). From 33.23-33.53m core is extremely clay alt'd (flt gg?) and lim. Foliations: 28.76m at 45°, 29.15m at 30°, 29.47m at 45°, 30.20m at 50°, 31.80m at 45°.	4					
10	34.30-299.31	34.20	49.20	GND is typical as seen in previous holes. GND has been mod ox'd with lim and cc/cb on frac faces. Core is very frac'd and broken up with comp pieces up to 35 cm (5x4x3 cm avg.). Locally core is mod cb alt'd from 39.98-40.17 m). Rare dark grey-black blebs that are fairly hard (~5) with v.f.g. specs (Aspy?) within qv's. Where ox'n is most intense, may have been previously ser alt'd as darker red-brown grains are very soft and non-cb. Slickenlines: 41.80m face 30°, lines 70°.	3					
10		49.20	62.48	GND is extensively clay alt'd through out and lim. Cb alt'n is also mod through out. GND is extensively weathered as, locally, core crumbles into sand (56.30-56.40). No shearing observed. Contact with non-clay alt'd GND is abrupt but crumbled. Qv'ing is minor and commonly displaced by frac's. Slickenlines: 52.12m face 30° lines 5°, at 62.00m face 5° lines 85°.	4			5	3	
10		62.48	112.78	GND is mod ox'd through out interval. Cb/cc frac's/frac filling is abundant through out core. Qv's tend to be heavily frac'd by cb (lim) frac's. Qv's are vuggy with lim staining (weathered sulphides). Silicified GND occurs locally at 62.88-63.38m with sharp contact to GND at 5° and is bery ox'd and vuggy. MGD bleb (74.52-74.60m) with frac'd contact and x-cut by qv's (mm-scale). From 83.92-84.31m core is very clay alt'd and cb-rich and lim with contacts at 45°. From 96.45-96.65m dark bio-rich MSED blocks are subangular. Fol'n occurson blocks (3x3x3 cm avg.) but no full diameter MSED core is present and can't be measured. Qv of unknown thickness occurs (>2cm). Qv is white with no mineralization. Slickenlines: 70.60m face 5° lines 80°, at 76.20m face 40° lines 30°, at 76.70m face 50° lines 80°, at 79.55m face 30° lines 40°, at 95.51m face 45° lines 60°, at 104.40m face 15° lines 60°, at 104.60m face 45° lines 5°, at 111.45m face 30° lines 60°, at 111.60m face 10° lines 80°, at 112.48m face 65° lines 65°.	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date:____September 6 - 11, 2005_____

LOGGED BY:___Kevin Piepgrass_____

PAGE 2 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
1	1	152.0	152.0	?														1.0				B365548	7.62	9.14	0.006			VA05083821	1.52
1	1	152.0	152.0	?														1.0				B365549	7.62	9.14	0.006	PD/CA		VA05083821	1.52
																						B365550	STANDARD 1A		0.888	1A		VA05083821	
1	1	2.0	2.0	45														2.0					9.14	10.67					1.53
1	1	3.0	3.0	60														1.0					15.24	16.76					1.52
0																						B365551	27.43	28.96	2.890			VA05083821	1.53
1	1	0.8	0.8	60														1.0				B365552	28.96	30.48	0.064			VA05083821	1.52
0																						B365553	30.48	32.00	0.053			VA05083821	1.52
0																						B365554	32.00	33.53	1.225			VA05083821	1.53
1	1	2.0	2.0	30														1.0				B365555	35.05	36.58	0.195			VA05083821	1.53
																						B365556	BLANK		<0.005			VA05083821	
1	1	1.0	1.0	30														1.0				B365557	36.58	38.10	0.021			VA05083821	1.52
1	1	0.8	0.8	60														1.0				B365558	38.10	39.62	0.034			VA05083821	1.52
1	1	1.0	1.0	35														1.0				B365559	39.62	41.15	0.526			VA05083821	1.53
1	1	0.8	0.8	35									0.1					1.0				B365560	41.15	42.67	0.059			VA05083821	1.52
1	1	0.8	0.8	35														1.0				B365561	42.67	44.20	0.816			VA05083821	1.53
																						B365562	42.67	44.20	0.045	DUP		VA05083821	1.53
3	1	0.5	1.5	35	70													2.0				B365563	44.20	45.72	0.246			VA05083821	1.52
2	1	0.7	1.2	35														2.0				B365564	45.72	47.24	0.050			VA05083821	1.52
0																						B365565	47.24	49.20	0.041			VA05083821	1.96
0																						B365566	49.20	50.29	0.033			VA05083821	1.09
0																						B365567	50.29	51.82	1.030			VA05083821	1.53
1	1	0.5	0.5	60														2.0				B365568	51.82	53.34	0.066			VA05083821	1.52
1	1	0.5	0.5	60														2.0				B365569	51.82	53.34	0.049	PD/CA		VA05083821	1.52
																						B365570	STANDARD 3C		0.092	3C		VA05083821	
1	1	0.5	0.5	60														2.0				B365571	53.34	54.86	0.053			VA05083821	1.52
1	6	0.3	0.3	40														99.0											
0																						B365572	54.86	56.39	0.068			VA05083821	1.53
1	1	1.0	1.0	30														2.0				B365573	56.39	57.91	0.074			VA05083821	1.52
0																						B365574	57.91	59.44	0.055			VA05083821	1.53
2	1	1.0	1.2	30														2.0				B365575	59.44	60.96	0.257			VA05083821	1.52
																						B365576	BLANK		<0.005			VA05083821	
1	1	0.2	0.2	30														1.0				B365577	60.96	62.48	0.490			VA05083821	1.52
1	1	0.7	0.7	50														2.0				B365578	62.48	64.01	0.576			VA05083821	1.53
1	3	0.3	0.3	5																80.0									
2	1	1.2	1.8	50														5.0				B365579	64.01	65.53	0.143			VA05083821	1.52
0																						B365580	65.53	67.06	0.292			VA05083821	1.53
3	1	0.5	1.2	60	30									0.1				2.0				B365581	67.06	68.58	0.159			VA05083821	1.52
3	1	0.5	1.2	60	30									0.1				2.0				B365582	67.06	68.58	0.237	DUP		VA05083821	1.52

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 3 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		112.78	125.06	GND is mod ox'd through out. Locally core is extremely ox'd and slightly cb (117.96-118.47). Extremely ox'd core is also slightly clay alt'd and full diameter core within interval are 2 massive py vn's with black sulphide (?). core is heavily frac'd through out interval. Stains with lim and cb in frac's are less common than previous intervals. Extremely clay alt'd core occurs locally at 118.95-119.08m. Frac'd blocks commonly have slickenlines but cannot be measured. Slickenlines: 114.20m face 10° lines 45°, at 115.72m face 50° lines 40°, at 121.03m face 30° lines 80°, at 124.40m face 45° lines 85°.	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
5	1	0.6	2.2	50		1.5	S	5	2				0.1					5.0				B365583	68.58	70.10	0.478			VA05083821	1.52
1	1	0.8	0.8	45						0.1								1.0				B365584	70.10	71.63	0.166			VA05083821	1.53
1	1	0.2	0.2	45														1.0				B365585	71.63	73.15	0.140			VA05083821	1.52
6	1	0.5	2.8	45	70																	B365586	73.15	74.68	0.605			VA05083821	1.53
2	1	0.3	0.5	50														2.0		2.0		B365587	74.68	76.20	0.059			VA05083821	1.52
1	1	0.5	0.5	50														2.0				B365588	76.20	77.72	0.068			VA05083821	1.52
1	1	0.5	0.5	50														2.0				B365589	76.20	77.72	0.035	PD/CA		VA05083821	1.52
																						B365590	STANDARD 4D		0.450	4D		VA05083821	
2	1	1.0	1.5	45														2.0				B365591	77.72	79.25	0.368			VA05083821	1.53
1	1	0.3	0.3	45														1.0				B365592	79.25	80.77	0.546			VA05083821	1.52
2	1	1.0	1.5	45														2.0				B365593	80.77	82.30	0.600			VA05083821	1.53
0																						B365594	82.30	83.82	1.480			VA05083821	1.52
1	1	0.5	0.5	45		0.5	S	5	3									2.0				B365595	83.82	85.34	0.094			VA05083821	1.52
																						B365596	BLANK		<0.005			VA05083821	
3	1	0.5	1.4	45	30	0.4	S	4	3													B365597	85.34	86.87	0.522			VA05083821	1.53
3	1	1.5	2.3	50														1.0				B365598	86.87	88.39	0.889			VA05083821	1.52
8	1	2.0	5.4	50	45	0.5	S	5	3									2.0				B365599	88.39	89.92	0.848			VA05083821	1.53
1	5	0.4	0.4	50		0.3	Q	5	3									5.0											
4	1	2.0	4.0	50		1.0	S	5	3	1.0								2.0				B365600	89.92	91.44	1.030			VA05083821	1.52
0																						B365601	91.44	92.96	0.141			VA05083821	1.52
0																						B365602	91.44	92.96	0.145	DUP		VA05083821	1.52
4	1	0.6	1.5	50														2.0				B365603	92.96	94.49	0.084			VA05083821	1.53
2	1	0.5	0.9	50														1.0				B365604	94.49	96.01	0.239			VA05083821	1.52
1	1	0.3	0.3	50														1.0				B365605	96.01	96.45	0.038			VA05083821	0.44
1	1	2.0	2.0	?																		B365606	96.45	96.65	0.020			VA05083821	0.20
2	1	1.2	1.6	50		0.5	S	5	3													B365607	96.65	97.54	0.692			VA05083821	0.89
2	1	0.5	1.0	50														1.0				B365608	97.54	99.06	0.401			VA05083821	1.52
2	1	0.5	1.0	50														1.0				B365609	97.54	99.06	0.288	PD/CA		VA05083821	1.52
																						B365610	STANDARD 5E		1.460	5E		VA05083821	
5	1	1.5	5.5	50	40	1.0	S	5	4									1.0				B365611	99.06	100.58	0.169			VA05083821	1.52
2	1	0.3	0.5	50														1.0				B365612	100.58	102.11	0.110			VA05083821	1.53
3	1	0.8	1.7	60	50													1.0				B365613	102.11	103.63	0.093			VA05083821	1.52
1	5	0.5	0.5	50		0.5	S/Q	4	1													B365614	103.63	105.16	0.425			VA05083821	1.53
3	1	2.0	2.8	50														2.0											
2	3	0.3	0.6	50						5.0							0.1	10.0									Mo		
4	1	0.7	2.0	50		3.0	Chl	4	2				0.1					1.0				B365615	105.16	106.68	0.309			VA05083821	1.52
																						B365616	BLANK		<0.005			VA05083821	
3	1	0.5	1.1	45	50	1.0	S	4	2	2.0								2.0				B365617	106.68	108.20	0.047			VA05083821	1.52
8	1	2.5	8.5	60	50													2.0				B365618	108.20	109.73	0.290			VA05083821	1.53
4	1	0.5	1.9	50	40													2.0				B365619	109.73	111.25	0.232			VA05083821	1.52
2	1	2.5	4.5	60		0.8	S	3	2				0.1					2.0				B365620	111.25	112.78	0.849			VA05083821	1.53
8	1	2.0	7.5	60	50					0.1								2.0				B365621	112.78	114.30	0.117			VA05083821	1.52
8	1	2.0	7.5	60	50					0.1								2.0				B365622	112.78	114.30	0.211	DUP		VA05083821	1.52
3	1	1.4	2.8	50	60								0.1					1.0				B365623	114.30	115.82	0.084			VA05083821	1.52
0																						B365624	115.82	117.35	0.209			VA05083821	1.53
1	1	2.0	2.0	50														1.0				B365625	117.35	117.96	0.409			VA05083821	0.61
2	6	1.0	1.5	65						50.0			40.0									B365626	117.96	118.47	0.714			VA05083821	0.51
1	1	0.5	0.5	45																		B365627	118.47	118.87	0.522			VA05083821	0.40
0																						B365628	118.87	120.40	0.075			VA05083821	1.53
0																						B365629	118.87	120.40	0.087	PD/CA		VA05083821	1.53
																						B365630	STANDARD 1A		0.806	1A		VA05083821	
0																						B365631	120.40	121.92	0.036			VA05083821	1.52
4	1	3.0	8.0	50														1.0				B365632	121.92	123.44	0.284			VA05083821	1.52
6	1	3.0	9.0	70	60																	B365633	123.44	125.06	0.246			VA05083821	1.62

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 5 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.06	128.02	GND is intensely ox'd mod frac'd (8 cm avg) and, for the most part, comp. Small intervals exist where core gradually fades into slightly ox'd, ser alt'd GND and then back into less ox'd GND (4). Possibly, intensely alt'd core was previously ser alt'd GND(?). Fresh ser alt'd GND occurs locally from 125.70-125.75m with sharp contacts at 60°. Clay alt'n occurs at uphole contact for 20 cm. Down hole contact fades into rel unalt'd GND with abundant lim frac selvages.	5	5				
10		128.02	137.31	GND is, for the most part, mod ox'd. Intervals of nearly unox'd GND are common (up to 30 cm) with sharp frac'd +/- slip contacts. Core is mod frac'd (8 cm avg). Cb/cc is common in/on frac's. At 128.74m within 12 cm qv is deep purple staining (Hem?) with massive py at edge of vn. Slickenlines: 129.15m face 45° lines 85°, at 131.92m face 45° lines 60°, at 138.30m face 15° lines 80°.	3					
10		137.31	153.92	GND appears fresh. Ox'n occurs as salveges along cb and lim frac's. However, GND is highly ox'dlocally with sharp contacts to fresh GND. GND is very slightly ser alt'd through out. At 141.05m a 1.2 cm qz/py vn (at 45° with 20% py) is sheared (multiple fracs and dissplacements) with 1.2 cm dextral dissplacement at 30°. The qv is also stretched into shear zone. Shear zone ~7 cm wide. Slickenlines are present at edge of shear zone: face 60° lines 2°. Within shear zone, ser alt'n is more intense (3). Another clay-rich shear zone at 145.07-145.12m present with fol'n at 70° and with slickenlines in two directions on the same face: 85° and 75°. From 145.12-146.60m core is heavily frac'd (no full diameter core) and highly ox'd. From 146.60-147.39m core is intensly ser alt'd with 4 dark red-brown (ox'd) cb-rich frac salveges at 30°. From 144.78-145.07m core is slightly ser and clay alt'd (lighter colour) with 5.5cm qz-po vn.Slip faces commonly have py smearing. Slickenlines are abundant through out. Slickenlines: 138.00m face 70° lines 70°, at 139.40 face 50° lines 50°, at 140.55 face 5° lines 50°, at 142.00m face 40° lines 45°, at 143.50m face 10° lines 30°, at 145.90m face 60° lines 20°, at 15	2	1				
10		153.92	161.27	GND is ox'd throughout and is heavily fractured (cm-scale blocks). fracs are 1mm, commonly w/ cb/cc.	2					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

094876

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
1	1	4.0	4.0	60														2.0				B365634	125.06	126.49	1.405			VA05083821	1.43
1	1	1.0	1.0	45														1.0				B365635	126.49	128.02	0.174			VA05083821	1.53
																						B365636	BLANK		<0.005			VA05083821	
4	1	1.2	2.5	45	80												0.1	2.0				B365637	128.02	128.58	0.157		Mo	VA05083821	0.56
1	1	12.0	12.0	45														1.0				B365638	128.58	128.70	6.900			VA05083821	0.12
1	1	0.5	0.5	50														1.0				B365639	128.70	129.54	0.103			VA05083821	0.84
4	1	1.2	4.0	45														1.0				B365640	129.54	131.06	0.090			VA05083821	1.52
2	1	2.0	3.0	45														1.0				B365641	131.06	132.59	0.149			VA05083821	1.53
2	1	2.0	3.0	45														1.0				B365642	131.06	132.59	0.137	DUP		VA05083821	1.53
1	1	0.2	0.2	30														1.0				B365643	132.59	134.11	0.140			VA05083821	1.52
3	1	3.0	4.1	45	60					1.0								2.0				B365644	134.11	135.88	0.418			VA05083821	1.77
1	1	27.0	27.0	35						1.0			0.1					2.0				B365645	135.88	136.15	9.660			VA05083821	0.27
3	1	0.4	1.0	50																		B365646	136.15	137.31	0.235			VA05083821	1.16
1	6	0.2	0.2	40		0.5	Q	4	1	50.0			5.0					10.0											
4	1	1.6	2.4	45	70	1.0	Q/S	5		2.0	2.0		0.1				0.1	1.0				B365647	137.31	138.68	0.052		Mo	VA05083821	1.37
1	3	0.5	0.5	45		0.5	Q/S	4	3																				
4	1	0.6	1.6	45		0.3	q	5		0.1	2.0		0.1									B365648	138.68	140.21	0.063			VA05083821	1.53
4	1	0.6	1.6	45		0.3	q	5		0.1	2.0		0.1									B365649	138.68	140.21	0.050	PD/CA		VA05083821	1.53
																						B365650	STANDARD 6F		2.650	6F		VA05083821	
3	1	1.0	2.0	45							2.0							1.0				B365651	140.21	141.73	0.179		sheared qtz vn/py	VA05083821	1.52
1	6	1.2	1.2	45						25.0																			
1	1	1.8	1.8	45														1.0				B365652	141.73	143.26	0.063			VA05083821	1.53
0																						B365653	143.26	143.66	0.018			VA05083821	0.40
0																						B365654	143.66	144.78	0.315			VA05083821	1.12
1	1	5.5	5.5	50						2.0	10.0	0.1	0.1									B365655	144.78	145.07	1.670			VA05083821	0.29
																						B365656	BLANK		<0.005			VA05083821	
4	1	2.0	3.6	50													0.1					B365657	145.07	146.60	0.462		Mo	VA05083821	1.53
4	1	0.4	1.4	50						1.0												B365658	146.60	147.39	0.682			VA05083821	0.79
3	1	1.2	1.8	50		0.5	5	4	3													B365659	147.39	148.20	1.100			VA05083821	0.81
4	1	0.4	1.6	50	85	1.6	s	5	1											1.0		B365660	148.20	149.35	0.851			VA05083821	1.15
5	1	0.5	2.0	45		1.0	s	4			1.0	0.1										B365661	149.35	150.88	0.192			VA05083821	1.53
5	1	0.5	2.0	45		1.0	s	4			1.0	0.1										B365662	149.35	150.88	0.743	DUP		VA05083821	1.53
2	1	4.0	5.0	50									0.1									B365663	150.88	152.40	0.773			VA05083821	1.52
5	1	3.0	45.0	45							1.0	0.1										B365664	152.40	153.92	2.740			VA05083821	1.52
5	1	2.0	3.5	45		0.3	q	5		0.1			0.1				0.1					B365665	153.92	155.45	0.137		Mo	VA05083821	1.53
7	1	2.0	5.0	45		0.4	s	4				0.1					0.1	1.0				B365666	155.45	156.97	1.485		Mo	VA05083821	1.52
2	1	2.0	2.5	45						1.0								1.0				B365667	156.97	158.50	0.072			VA05083821	1.53
2	1	1.4	1.8	45						1.0								1.0				B365668	158.50	160.02	0.237			VA05083821	1.52
1	5	0.3	0.3	45														1.0											
2	1	1.4	1.8	45						1.0								1.0				B365669	158.50	160.02	0.140	PD/CA		VA05083821	1.52
1	5	0.3	0.3	45														1.0											
																						B365670	STANDARD 3C		0.090	3C		VA05083821	
2	1	0.5	1.0	45																		B365671	160.02	161.27	0.185			VA05083821	1.25

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005 PAGE 1 of 12	
DRILL HOLE # : DG05 - 308C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd; Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION From → To:	From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.27	182.88	grey GND that's very slightly ser +/- chl alt'd throughout. core is v.comp throughout. locally core is heavily fractured and lim from 166.12-167.50m. shear zone occurs at 167.35m (3-5cm) w/ foliations at 40°. frac faces/fills are still lim commonly w/ cb/cc. non-ox'd fracs do occur but are rare and commonly contain fresh po w/ tr cpy. qtz vn generally contain 1-10% chl (not classified as qtz/chl vns-5). slickenlines: at 163.84m face 50° lines 60°; at 164.95m face 60° lines 50°; at 167.75m face 45° lines 80°; at 173.64m face 60° lines 80°; at 182.78m face 60° lines 90°.		1				
10		182.88	198.12	GND similar to interval 161.27-182.88m as previously described. large intervals of intense ser alt is common. where ser alt'd GND is in contact w/ rel unalt'd GND there tends to be a transition zone of darker green alt (chl) from 1-4cm. from 185.51-185.99m, 2 large qtz vns (19 & 17cm). Slickenlines: 193.57m face 15° lines 40° at 193.63m face 40° lines 40°.	1					
10		198.12	208.79	GND is very slightly ser alt'd through out. Core is comp. Frac's / frac fills are cb and ser +/- chl. Lim is no longer observed within frac's.		1				
10		208.79	211.84	Grey GND that has been mod clay alt'd and slightly ser alt'd. Up hole contact is gradual. At 211.45-211.84m GND is silicified with a shallow (15°), sharp contact. Qv's tend to be irregular +/- displaced (no fol'n). Slickenlines: 209.25m face 45° lines 85° at 211.12m face 5° lines 70°, at 211.65m face 30° lines 60°.		2		3		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

PAGE 8 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
7	1	2.0	8.5	45		0.6	q/s	5	1		0.1						0.1					B365672	161.27	163.07	0.096		Mo	VA05083821	1.80
4	1	2.3	3.8	45	65	0.5	s	3														B365673	163.07	164.59	0.034			VA05083821	1.52
2	1	0.3	0.6	45		4.0	q/s/chl	5		1.0	1.0											B365674	164.59	166.12	0.163		py found w/in cb bleb	VA05083821	1.53
0																						B365675	166.12	167.64	0.603			VA05083821	1.52
																						B365676	BLANK		<0.005			VA05083821	
2	1	0.5	0.9	45		0.4	S/Q	3			1.0	0.1	0.1							2.0		B365677	167.64	169.16	0.067			VA05083821	1.52
2	1	1.5	1.7	45		1.2	q/chl	5			1.0		1.0									B365678	169.16	170.69	0.098			VA05083821	1.53
1	5	0.2	0.2	40							2.0																		
1	1	0.3	0.3	45																		B365679	170.69	172.21	0.023			VA05083821	1.52
3	1	0.7	1.6	45		0.2	q	5			4.0	0.1										B365680	172.21	173.74	0.046			VA05083821	1.53
8	1	2.0	6.5	45	45	0.4	q	5			4.0	0.1					0.1					B365681	173.74	175.26	0.050		qtz vn at 45°, x-cut qtz vn at 135°; 0.1 mo	VA05083821	1.52
8	1	2.0	6.5	45	45	0.4	q	5			4.0	0.1					0.1					B365682	173.74	175.26	0.021	DUP	qtz vn at 45°, x-cut qtz vn at 135°; 0.1 mo	VA05083821	1.52
3	1	0.6	1.5	45		0.4	s/q	5			4.0		0.1				0.1					B365683	175.26	176.78	0.038		Mo	VA05083821	1.52
2	5	0.2	0.2	45		0.3	q	5			5.0		0.1																
6	1	1.4	3.0	45		0.4	q	5			5.0	0.1	0.1				0.1			1.0		B365684	176.78	178.31	0.042		Mo	VA05083821	1.53
3	1	0.4	1.0	45	40	0.3	q	5			4.0	1.0										B365685	178.31	179.83	0.129			VA05083821	1.52
2	1	0.4	0.8	45		0.4	q/chl	5			2.0											B365686	179.83	181.36	0.021			VA05083821	1.53
2	1	1.0	1.4	45							4.0	1.0										B365687	181.36	182.88	0.716			VA05083821	1.52
5	1	2.0	3.4	45	30	0.3	q	5			4.0	0.1										B365688	182.88	184.40	0.452			VA05083821	1.52
5	1	2.0	3.4	45	30	0.3	q	5			4.0	0.1										B365689	182.88	184.40	0.547	PD/CA		VA05083821	1.52
																						B365690	STANDARD 7G		4.370	7G		VA05083821	
6	1	1.2	2.4	40	50					1.0	2.0		1.0									B365691	184.40	185.51	0.197		Mo	VA05083821	1.11
2	1	19.0	36.0	50	35					12.0	2.0		5.0	1.0	2.0		0.1					B365692	185.51	185.99	9.350			VA05083821	0.48
7	1	2.0	5.0	40	50					2.0			0.1									B365693	185.99	187.02	0.557			VA05083821	1.03
1	1	0.2	0.2	45							2.0											B365694	187.02	187.97	0.251			VA05083821	0.95
3	1	0.5	1.2	45							1.0						0.1					B365695	187.97	188.98	0.153		Mo	VA05083821	1.01
																						B365696	BLANK		<0.005			VA05083821	
5	1	1.0	2.1	45		1.0	S/Q	5		0.1	1.0											B365697	188.98	190.50	0.036			VA05083821	1.52
1	5	1.0	1.0	45		0.3	Q/CHL	5																					
4	1	1.2	3.8	45		1.5	Q/CHL	5		0.1	1.0											B365698	190.50	192.02	0.041			VA05083822	1.52
2	1	0.8	1.3	45		1.0	Q/S	5			2.0	0.1										B365699	192.02	192.85	0.287			VA05083822	0.83
1	6	2.5	2.5	45						2.0			2.0		2.0							B365700	192.85	193.04	0.493			VA05083822	0.19
4	1	3.0	4.5	45	30	2.0	S/CHL	5		0.1	2.0											B365701	193.04	194.35	0.443			VA05083822	1.31
4	1	3.0	4.5	45	30	2.0	S/CHL	5		0.1	2.0											B365702	193.04	194.35	0.244	DUP		VA05083822	1.31
1	1	0.3	0.3	45		0.2	A/Q	5			2.0											B365703	194.35	195.86	0.018			VA05083822	1.51
3	1	2.5	3.5	5	45					0.1	1.0	0.1					0.1			0.1		B365704	195.86	197.48	0.015		Mo	VA05083822	1.62
3	1	1.0	2.0	50	10						1.0											B365705	197.48	198.12	0.524			VA05083822	0.64
4	1	0.5	1.5	45	30						1.0											B365706	198.12	199.64	0.048			VA05083822	1.52
6	1	1.0	3.1	40							2.0											B365707	199.64	201.17	0.106			VA05083822	1.53
1	1	0.6	0.6	45		0.3	Q/S	5			4.0	0.1					0.1					B365708	201.70	202.69	0.111		Mo	VA05083822	0.99
1	1	0.6	0.6	45		0.3	Q/S	5			4.0	0.1					0.1					B365709	201.70	202.69	0.123	PD/CA		VA05083822	0.99
																						B365710	STANDARD 2B		3.000	2B		VA05083822	
5	1	0.6	2.2	40		0.5	Q/S	5			3.0	0.1										B365711	202.69	204.22	0.026			VA05083822	1.53
4	1	0.5	2.4	35		1.0	Q/S	5			4.0	0.1										B365712	204.22	205.74	0.156			VA05083822	1.52
5	1	4.0	9.5	35		0.5	S	5			2.0						Mo/.1					B365713	205.74	207.26	0.592			VA05083822	1.52
1	3	0.5	0.5	40		0.5	Q/S	5		0.1	1.0																		
4	1	1.0	2.5	40		1.0	Q/S	5			4.0											B365714	207.26	208.79	0.127			VA05083822	1.53
1	1	0.5	0.5	45																		B365715	208.79	210.31	0.033			VA05083822	1.52
																						B365716	BLANK		<0.005			VA05083822	
0																						B365717	210.31	211.84	0.163			VA05083822	1.53

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 9 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		211.84	233.76	Grey GND has been very slightly ser alt'd. Core is comp. Frac's / frac faces contain cb/cc and ser. Locally frac'ing is more abundant (ie. 222.50-225.55m). Diss py and smeared py are common on frac faces and slip faces (with Chl). At 211.77m a 0.5 cm qv shows 1 cm sinistral displacement along a 2° cb/ser frac. At 218.11m a 30° cc frac contains 20% Po and 2% Cp. mm-scale stringers of qtz-chl-po are common. Slickenlines: 213.30m face 5° lines 80°, at 218.60m face 5° lines 80°, at 223.40m face 30° lines 50°, at 224.13m face 50° lines 10°, at 228.20m face 20° lines 20°.		1				
10		233.76	239.27	GND is intensely ser alt'd except for minor intervals of mod ser alt'd GND. Mod clay alt'n occurs locally from 234.28-238.41m and contains fine grained, euhedral diss py (5%). QV within interval is softer and slightly irregular. Slickenlines tend to be distinct with smeared py. Diss py occurs through out ser alt'd core ~1% along with a trace of aspy. QV are commonly displaced (up to 1.5 cm) by shallow frac's. Slickenlines: 235.01m face 80° lines 80°, at 235.11m face 20° lines 85°, at 236.25m face 10° lines 60°, at 236.64m face 45° lines 2° at 237.45m face 30° lines 85°.		5				
10		239.27	251.46	Grey GND is very slightly ser +/- chl alt'd. Intense ser alt'd core occurs locally [5] (up to 33cm). Intense ser alt. appears to be associated with fracturing (pre-qv) and qv develop within fractures as ser selvages are of different thickness on either side of qv and fractures are adjacent to qv. MGD occurs from 249.70-250.29 and is f.g. MGD also appears ser alt'd throughout. contact with grey GND is gradual. 1-2mm vnlts with 1-10% chl are common and tent to be po +/- aspy-rich (10-20%). F-mg euhedral and smeared py common on fracture and slip faces. Slickenlines: at 243.25m face 45° lines 75°, at 244.65m face 15° lines 45°, and at 249.12m face 5° lines 30°. At 245.26m a felsic dyke (2.5cm) cuts through GND at 15%. Dyke is qtz rich with 5° f.g. bio x-cut by qv.		1	1			
10		251.46	272.23	Grey GND is slightly clay alt'd and very slightly ser alt'd. Plag grains are abundant and are soft and white. Core is highly fractured (cb/cc filled with ser). Q.V.s tend to be highly fractured (cc) commonly with mm-scale displacement. QV also tend to have 0-10% chl. Blocks of very slightly ser/chl alt'd GND occur with slip faces on contacts. Slickenlines: at 254.10m face 40° lines 75°, at 257.16m face 10° lines 30°, at 257.36m face 60° lines 5°, at 265.15m face 20° lines 60°, at 270.00m face 40° lines 70°, and at 271.01m face 20° lines 45°.		1		2		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
3	1	0.5	1.5	30	40	1.2	S	5			1.0											B365718	211.84	213.36	0.060			VA05083822	1.52
1	5	0.6	0.6	30		0.5	S/Q	5		0.1	1.0																		
4	1	1	1.7	30		0.3	Q	5			4											B365719	213.36	214.88	0.069			VA05083822	1.52
2	1	0.6	1.2	30		0.5	Q/S	5			4.0											B365720	214.88	216.41	0.237			VA05083822	1.53
3	1	1.0	1.8	30	35						3.0											B365721	216.41	217.93	0.030			VA05083822	1.52
3	1	1.0	1.8	30	35						3.0											B365722	216.41	217.93	0.056	DUP		VA05083822	1.52
2	1	1.0	1.5	45	30						2.0											B365723	217.93	219.46	0.029			VA05083822	1.53
2	1	0.6	1.1	35		1.0	s	5			4.0	1.0										B365724	219.46	220.98	0.164			VA05083822	1.52
4	1	1.0	2.8	35		1.0	q/s	5			2.0	0.1										B365725	220.98	222.50	0.098			VA05083822	1.52
1	1	0.4	0.4	35							1.0											B365726	222.50	224.03	0.165			VA05083822	1.53
4	1	0.4	1.3	35	45	0.5	s	5		0.1	2.0											B365727	224.03	225.55	0.105			VA05083822	1.52
2	1	0.4	7.0	35							3.0											B365728	225.55	227.08	0.066			VA05083822	1.53
2	1	0.4	7.0	35							3.0											B365729	225.55	227.08	0.034	PD/CA		VA05083822	1.53
																						B365730	STANDARD 5E		1.335	5E		VA05083822	
3	1	0.5	1.1	45	40	0.4	q/s	5		0.1	2.0											B365731	227.08	228.60	0.504			VA05083822	1.52
10	1	0.6	4.0	45	30					0.1	4.0						Mo/.1					B365732	228.60	230.12	0.071		A 5° qv x-cuts all vn's. 45° vn's are in ser alt'd core.	VA05083822	1.52
4	1	1.0	4.0	45	60						3.0											B365733	230.12	231.65	0.337			VA05083822	1.53
5	1	0.5	1.5	45	35						4.0											B365734	231.65	233.17	0.274			VA05083822	1.52
1	5	0.4	0.4	30							5.0											B365735	233.17	233.76	0.037			VA05083822	0.59
																						B365736	BLANK		<0.005			VA05083822	
8	1	0.7	2.7	45	30					8.0												B365737	233.76	234.70	0.676			VA05083822	0.94
3	1	0.5	1.3	45	60					2.0												B365738	234.70	236.22	0.083		Py in vn's occur in blebs	VA05083822	1.52
1	6	1.0	1.0	88						15.0	40.0				1.0														
5	1	1.0	3.1	45	60					1.0	2.0											B365739	236.22	237.74	2.660			VA05083822	1.52
1	6	1.7	1.7	55						50.0																			
6	1	0.8	3.0	45	30					0.1	2.0	0.1										B365740	237.74	239.27	0.182			VA05083822	1.53
5	1	5.0	6.0	45		1.0	s	5		1.0	3.0		1.0									B365741	239.27	240.79	0.285			VA05083822	1.52
5	1	5.0	6.0	45		1.0	s	5		1.0	3.0		1.0									B365742	239.27	240.79	0.767	DUP		VA05083822	1.52
7	1	1.0	2.8	45	30	1.0	s/q	5		1.0	5.0	1.0										B365743	240.79	242.32	0.802			VA05083822	1.53
2	6	2.0	2.3	55	45	0.5	q	5		15.0	5.0		20.0														po only in 0.3cm sx		
8	1	2.2	5.5	45		1.0	s/q	5		0.1	5.0	0.1										B365744	242.32	243.84	0.074			VA05083822	1.52
6	1	1.2	2.6	45		0.4	5	5			2.0	0.1										B365745	243.84	245.36	0.369			VA05083822	1.52
2	1	0.5	0.7	45		1.0	s	3			2.0	0.1	5.0									B365746	245.36	246.89	0.030		aspy only occurs in	VA05083822	1.53
4	1	0.5	1.8	45	10	1.0	s/q	4			2.0	0.1										B365747	246.89	248.41	0.032			VA05083822	1.52
3	1	0.6	1.3	45							2.0											B365748	248.41	249.70	0.080			VA05083822	1.29
3	1	0.6	1.3	45							2.0											B365749	248.11	249.70	0.074	PD/CA		VA05083822	1.59
																						B365750	STANDARD 4D			4D	SAMPLE???	VA05083822	
3	1	0.5	1.4	40		0.4	s	5			5.0	0.1	0.1									B365751	249.70	250.29	0.375			VA05083822	0.59
5	1	1.5	3.1	45							2.0	0.1										B365752	250.29	251.46	0.104			VA05083822	1.17
6	1	1.5	3.2	45	30	0.5	s	2			2.0											B365753	251.46	252.98	0.057			VA05083822	1.52
5	1	0.7	2.4	50		0.4	5	3			2.0	0.1										B365754	252.98	254.51	0.068			VA05083822	1.53
4	1	0.5	1.6	60							3.0											B365755	254.51	256.03	0.058			VA05083822	1.52

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 11 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		272.23	277.20	GND is very slightly ser and chl alt'd. Core is competent. Up hole contact is gradual. Down hole contact is sharp (frac) at 40°. From 274.98-276.06m core is intensely ser alt'd. <2mm chl/po vnlts are common. Slickenlines: at 273.37m face 45° lines 30°, and at 275.18m face 60° lines 80°.		1	1			
10		277.20	294.50	GND same as previously described from interval 251.46-272.23m.Locally core is moderately clay alt'd (277.20-277.37m). Intense clay alt'd core from 277.20-277.37m contains diss, ox'd py (?). (Diss py has been observed in previous DDHs where clay alt'n is intense). From 280.99-281.45m core is intensely ser alt'd and also intensely clay alt'd. Q.V. are irregular and displaces (no shear fol'n observed). cb fracture at 15° displaces 2 avs by 5cm(293.53m). Slickenlines: at 277.45m face 5° lines 30°, at 280.80m face 20° lines 85°, at 282.45m face 5° lines 85°, at 287.11m face 30° lines 80°, at 288.34 face 50° lines 10°, at 292.00m face 20° lines 50°, and at 293.53m face 45°-10° (irregular) lines 85°.		1		2		
10		294.50	299.31	GND is very slightly ser and chl alt'd, same as previously described from interval 272.24-277.20m Slickenlines: at 295.43m face 65° lines 65°, and at 299.29m face 30° lines 75°.		1	1			
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
																						B365756	BLANK		<0.005			VA05083822	
5	1	1.0	4.0	60							2.0		0.1									B365757	256.03	257.56	0.192			VA05083822	1.53
4	1	1.0	3.0	50	60	1.0	5	3			2.0											B365758	257.56	259.08	0.074			VA05083822	1.52
3	1	1.0	2.0	60							2.0	0.1										B365759	259.08	260.60	0.107			VA05083822	1.52
2	1	1.4	1.8	60						0.1	2.0	0.1										B365760	260.60	262.13	0.413			VA05083822	1.53
3	1	1.0	2.2	60							3.0	1.0										B365761	262.13	263.85	0.383			VA05083822	1.72
3	1	1.0	2.2	60							3.0	1.0										B365762	DUPLICATE		0.144	DUP		VA05083822	
3	1	1.4	2.3	60	50						2.0											B365763	263.85	265.18	0.048			VA05083822	1.33
5	1	0.5	2.0	60		0.5	s	3			2.0											B365764	265.18	266.70	0.081			VA05083822	1.52
3	1	4.0	4.8	60		0.5	s	4		0.1	2.0											B365765	266.70	268.22	0.588			VA05083822	1.52
4	1	0.6	1.6	60	30	1.0	s/q	5			1.0											B365766	268.22	269.75	0.031			VA05083822	1.53
2	1	1.0	1.4	60	30						1.0											B365767	269.75	271.27	0.031			VA05083822	1.52
6	1	1.0	3.0	60	45	1.0	s	2			3.0											B365768	271.27	272.23	0.215			VA05083822	0.96
6	1	1.0	3.0	60	45	1.0	s	2			3.0											B365769	271.27	272.23	0.275	PD/CA		VA05083822	0.96
																						B365770	STANDARD 3C		0.090	3C		VA05083822	
1	1	0.3	0.3	60							2.0	0.1										B365771	272.23	272.80	0.025			VA05083822	0.57
4	1	0.5	1.8	60	20						3.0	0.1										B365772	272.80	274.32	0.070			VA05083822	1.52
1	1	0.6	0.6	45							15.0	1.0	0.1									B365773	274.32	274.98	0.096			VA05083822	0.66
5	1	1.0	2.3	45	60					1.0	1.0											B365774	274.98	276.06	0.079			VA05083822	1.08
1	6	0.5	0.5	50						20.0																			
1	1	1.0	1.0	60							1.0											B365775	276.06	277.20	0.043			VA05083822	1.14
																						B365776	BLANK		<0.005			VA05083822	
2	1	0.5	0.9	45							1.0											B365777	277.20	278.89	0.044			VA05083822	1.69
0																						B365778	278.89	280.42	0.146			VA05083822	1.53
1	1	0.8	0.8	45																		B365779	280.42	281.94	0.104			VA05083822	1.52
1	1	0.4	0.4	50							1.0											B365780	281.94	283.46	0.162			VA05083822	1.52
3	1	0.4	1.1	60	50					0.1	1.0											B365781	283.46	284.99	0.032			VA05083822	1.53
1	6	0.3	0.3	60						20.0																			
3	1	0.4	1.1	60	50					0.1	1.0											B365782	283.46	284.99	0.020	DUP		VA05083822	1.53
1	6	0.3	0.3	60						20.0																			
2	1	0.5	0.7	60							2.0	0.1										B365783	284.99	286.51	0.023			VA05083822	1.52
0																						B365784	286.51	288.04	0.289			VA05083822	1.53
3	1	0.5	1.2	30	60	0.5	s	3			1.0	0.1										B365785	288.04	289.56	0.036			VA05083822	1.52
2	1	1.0	1.5	60		0.4	s	4			1.0											B365786	289.56	291.08	0.048			VA05083822	1.52
1	1	0.4	0.4	60							1.0											B365787	291.08	292.61	0.027			VA05083822	1.53
4	1	1.5	3.0	60							1.0											B365788	292.61	294.50	0.037			VA05083822	1.89
4	1	1.5	3.0	60							1.0											B365789	292.61	294.50	0.040	PD/CA		VA05083822	1.89
																						B365790	STANDARD 2B		2.920	2B		VA05083822	
1	1	0.6	0.6	50							0.1											B365791	294.50	295.66	0.129			VA05083822	1.16
2	1	0.7	1.0	60	50						1.0											B365792	295.66	297.18	0.122			VA05083822	1.52
3	1	1.0	2.0	60	40						1.0											B365793	297.18	298.70	0.027			VA05083822	1.52
2	1	1.0	2.0	45							1.0											B365794	298.70	299.31	0.100			VA05083822	0.61
																						EOH	EOH	EOH					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-309C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1070m

BEARING: 000 | DIP: -50°

DATES DRILLING: September 1 - 8, 2005 | DATES LOGGING: September 8 - 12, 2005

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459799 NORTHING: 7099237

COORD SYSTEM: NAD 83: EASTING: 459680 NORTHING: 7099422

NAD 27 (CORRECTED for historic grid): EASTING: 459769 NORTHING: 7099247

SECTION LINE (historic grid): 459775 E

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden:

Deviation:

Casing: 8.53m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0	8.53	Csg; No recovery
8.53	274.62	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B365128-B365200, B365800-B365826

Requisition #: MASP448STRGOL.05Q | Date Shipped: 16-Sep-05

Lab Record #: VA05082983 | Date Received: 27-Sep-05

Sample Sequence: B365827-B365964

Requisition #: MASP448STRGOL.05Q | Date Shipped: 17-Sep-05

Lab Record #: VA05085049 | Date Received: 29-Sep-05

Duplicates:	365142; 365162; 365182; 365802; 365822; 365842; 365862; 365882; 365902; 365922; 365942; 365962
Preparation Duplicate/ Check Assay:	365129; 365149; 365169; 365189; 365809; 365829; 365849; 365869; 365889; 365909; 365929; 365949
Standards:	365130 (6F); 365150 (3C); 365170 (5E); 365190 (4D) 365810 (7G); 365830 (3C); 365850 (7G); 365870 (1A); 365890 (5E); 365910 (4D); 365930 (7G); 365950 (2B)
Blanks:	365136; 365156; 365176; 365196; 365816; 365836; 365856; 365876; 365896; 365916; 365936; 365956

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	DIP (+ 27 Corr)
106.67	334.9	-48.9	0.9	1.9
185.92	335.9	-47.8	1.9	2.9
274.31	339.0	-46.0	5.0	6.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 1-8, 2005	PAGE 1 of 12		
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-8.53			CASING - no recovery						
10	8.53 - 274.62	8.53	15.24	GND. Unalt'd except minor oxidation and selvages around few qtz veins. Recovery is poor.	2	1				
10		15.24	21.34	Fine-grained GND; colour is greyish-beige (dry). Oxidation is pervasive.	4	1				
10		21.34	22.68	GND, all stained orange-brown except 2 small 'blue' sections of un-limonized GND, 4cm and 2cm wide. Even qtz in veins is orangey brown. Crumbly gravel texture toward end of sample.	4			1		
10		22.68	30.00	Very crumbly and broken up. Completely limonite-covered, even in otherwise unalt'd GND. Pieces up to 20cm long, but no full-diameter core. Very little clay (<5%), but very gravely to coarse sand-texture.	5	1			3	
10		30.00	34.27	Competent but weak GND. Moderately limonized and carbonitized. Veins and fractures are highly limonized with ox'd selvages. GND texture is normal - med. grained.	3				2	
10		34.27	38.40	Very crumbly, broken, limonized GND. No complete-diameter core. 60% reduced to sand and <1cm chunks of GND and qtz eyes.	4	1		1	1	
10		38.40	50.05	Competent, slightly limonized, med-grained GND. Veins are very thin, <1cm, @~30° to CA, with ox'd Fe-minerals to orange-red within veins. One different set in one interval are all ~1cm thick and appear more as silicified zones (minor bt within is disseminated). Minor hematite in veins as well (ox'd purple-black).	1	1			1	
10		50.05	57.69	Very fine-grained, silicious GND. Pale grey and uniform to ~55m. Few veins. 1cm qtz vein at 55m has slightly more silicified-than-surrounding selvage. Nearby carbonate/limonite vein has intensely orange-brown selvage, uniform for 20cm surrounding. No mineralization. Uniform ox'd orangey brown to end of section	4				2	
10		57.69	68.58	Med-grained GND with minor to moderate limonite staining; some patches of 'blue' GND ~3-5cm in diameter.	2				1	2

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides										Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	70		2.0	cb	2	3									3.0				B365128	8.53	9.14	0.035			VA05082983	0.61
1	1	0.5	0.5	70		2.0	cb	2	3									3.0				B365129	8.53	9.14	0.037	PD/CA		VA05082983	0.61
																						B365130	STANDARD 6F		2.760	6F		VA05082983	
																						B365131	9.14	10.67	0.020			VA05082983	1.53
																						B365132	10.67	12.19	0.037			VA05082983	1.52
																						B365133	12.19	13.72	0.016			VA05082983	1.53
																						B365134	13.72	15.24	0.056			VA05082983	1.52
																						B365135	15.24	16.76	0.025			VA05082983	1.52
																						B365136	BLANK		<0.005			VA05082983	
																						B365137	16.76	18.29	0.036			VA05082983	1.53
																						B364138	18.29	19.81	0.065			VA05082983	1.52
6	1	1.5	3.5	40	60					0.1							0.1	2.0				B365139	19.81	21.34	0.137			VA05082983	1.53
2	1	1.5	2.0	50		4.0	q	5	4									3.0				B365140	21.34	22.68	0.373			VA05082983	1.34
																						B365141	22.68	23.20	0.052			VA05082983	0.52
																						B365142	22.68	23.20	0.049	DUP		VA05082983	0.52
1	1	0.5	0.5	40		1.0	cb	4	3													B365143	23.20	24.38	0.033			VA05082983	1.18
																						B365144	24.38	25.91	0.033			VA05082983	1.53
2	1	0.6	1.0	40		1.0	q	2	2									1.0				B365145	25.91	27.43	0.437			VA05082983	1.52
1	1	0.3	0.3	40		0.5	q	2	2									2.0				B365146	27.43	28.96	0.047			VA05082983	1.53
																						B365147	28.96	30.00	0.104			VA05082983	1.04
																						B365148	30.00	30.48	0.136			VA05082983	0.48
																						B365149	30.00	30.48	0.142	PD/CA		VA05082983	0.48
																						B365150	STANDARD 3C		0.088	3C		VA05082983	
2	1	0.4	0.8	50		1.0	q	3	3													B365151	30.48	32.00	0.084		lim. ox'n w/in vein	VA05082983	1.52
1	4	1.0	1.0	65																									
																						B365152	32.00	33.53	0.111			VA05082983	1.53
																						B365153	33.53	34.27	0.018			VA05082983	0.74
																						B365154	34.27	35.05	0.044			VA05082983	0.78
1	1	0.5	0.5	50		2.0	q/cb	4	2													B365155	35.05	36.58	0.080			VA05082983	1.53
																						B365156	BLANK		<0.005			VA05082983	
																						B365157	36.58	37.40	0.021			VA05082983	0.82
																						B365158	37.40	38.40	0.025			VA05082983	1.00
2	1	0.4	0.8	5	40	1.0	q/cb	4	3									20.0				B365159	38.40	39.42	0.024			VA05082983	1.02
2	1	0.5	0.8	40		1.0	q/cb	4	2									3.0				B365160	39.62	41.15	0.056			VA05082983	1.53
5	1	1.0	5.0	110	120	1.0	q	2	1											2.0									
2	1	0.3	0.6	30		0.5	q/cb	3	3									5.0				B365161	41.15	42.67	0.045			VA05082983	1.52
2	1	0.3	0.6	30		0.5	q/cb	3	3									5.0				B365162	41.15	42.67	0.015	DUP		VA05082983	1.52
2	1	0.4	0.7	30		2.0	q/s	2	4									30.0				B365163	42.67	44.20	0.312			VA05082983	1.53
2	1	0.7	1.2	0	35	1.0	q	4	3								2.0	10.0				B365164	44.20	45.72	0.025		grey qtz, moly	VA05082983	1.52
3	1	1.0	2.3	30		2.0	q/cb	4	3									3.0		3.0		B365165	45.72	47.24	0.041			VA05082983	1.52
1	1	0.4	0.4	35		4.0	q/s/cb	4	4								5.0	5.0				B365166	47.24	48.77	0.015		moly	VA05082983	1.53
5	1	0.6	3.0	30	45	4.0	q/cb	4	4									3.0				B365167	48.77	50.05	0.219			VA05082983	1.28
4	1	0.6	1.2	50	30	4.0	q/cb	5	2									5.0				B365168	50.05	50.80	0.714			VA05082983	0.75
4	1	0.6	1.2	50	30	4.0	q/cb	5	2									5.0				B365169	50.05	50.80	1.315	PD/CA		VA05082983	0.75
																						B365170	STANDARD 5E		1.470	5E		VA05082983	
2	1	0.6	1.0	30		3.0	q/cb	4	4													B365171	50.80	51.82	0.211			VA05082983	1.02
																						B365172	51.82	53.34	0.053			VA05082983	1.52
																						B365173	53.34	54.86	0.030			VA05082983	1.52
2	1	1.0	1.4	50		10.0	q	1	5									1.0				B365174	54.86	56.39	0.302			VA05082983	1.53
1	4	0.4	0.4	30		20.0	cb/lim	5	5																				
4	1	1.2	3.0	60					5									10.0				B365175	56.39	57.69	0.335			VA05082983	1.30
1	3	2.0	2.0	60		6.0	cb	5	5								0.1	15.0											
							lim	4														B365176	BLANK		<0.005			VA05082983	
4	1	0.8	2.3	50		2.0	cb/q	4	5								2.0	5.0				B365177	57.69	58.71	0.068			VA05082983	1.02

DRILL LOG LEGEND P1	DATE: September 1-8, 2005 PAGE 3 of 12		
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		68.58	80.50	Moderately ox'd GND; oxidation especially concentrated around veins and fracture infills (limonite). Competent core, regular breakage at 40° and 135° to CA. 'Other' sulphide noted throughout last section, and occurring more massively here - few veins contain >5% of it. Silver, submetallic lustre to dull grey; appears massive or flakey (micaceous), soft (2-3).	3	1			1	
10		80.50	89.92	Oxidation moderate to strong - thick crumbly to flattened (carb-rich) limonite covers most faces and can also be seen within GND matrix. Qtz veins have poor mineralization and contain only brown-black oxidation products. Fresh py (trace) seen in one vein. Recovery is good.	4	1			3	
10		89.92	92.96	Unalt'd, competent medium-grained GND with minor oxidation in 'selvages' surrounding limonitic fracture infills. This is the largest section of 'blue' GND in hole down to this point. Good mineralization within qtz veins at 20-40° to CA.	1				1	
10		92.96	98.89	Limonite returns pervasively. Rock broken into <10cm pieces to 97.4m. Recovery poor from 94.49 to 96.01m. Few 'blue' patches ~5cm in diameter at 98.5m - irregular boundaries due to lim. stained selvages around fractures.	4				2	
10		98.89	105.16	Even more limonite here. Opaque and uniform around veins. GND texture 20% erased into medium orange brown.	4	1			1	
10		105.16	117.35	Pervasively limonite-stained GND. Brown. Weak rock. Broken along parallel to CA (length-wise to core), and at 90° to CA, regularly. As well, fractures at random angles in between 0 and 90°. Gouge material (brecciated GND in clay to fine sand texture) for 15cm at 109.50m. Other evidence of motion in truncated veins (no direction avail.) along fracture. Sericitic alteration in wide selvages around lim-stained qtz/carb veins and totally oxidized sulphide veins. More gouge at 115.95 to 116.20m. Where selvages are not noted, they are not visible due to pervasive oxidation through section.	4	2			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: September 1-8, 2005

LOGGED BY: M. Stone

#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Selvages Alteration	Selvages (0-5)	Ox. State 0-5	Sulphides pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation oxide	scoordite	biotite	other	Sample Number	Interval From	Interval To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	1	2.0	2.0	50		2.0	cb/q	4	3	0.1							0.1	6.0				B365178	58.71	59.44	**0.137**			VA05082983	0.73
3	1	0.5	1.1	40		2.0	cb/q	4	3								0.1	4.0				B365179	59.44	60.96	**0.023**			VA05082983	1.52
2	3	1.0	1.3	30		4.0	cb/q	4	4																				
							lim	5																					
3	1	1.0	2.2	40		2.0	q/cb	4	3								0.1	2.0				B365180	60.96	62.48	**0.268**			VA05082983	1.52
							lim																						
3	1	1.0	3.0	30	50	3.0	q	3	3									2.0				B365181	62.48	64.01	**0.281**			VA05082983	1.53
1	6	1.0	1.0	50		4.0	q/cb	2	4									100.0											
1	6	1.0	1.0	50		4.0	q/cb	2	4									100.0				B365182	62.48	64.01	**0.808**	DUP		VA05082983	1.53
2	1	1.0	1.5	50		2.0	cb	1	4									2.0				B365183	64.01	65.53	**0.050**			VA05082983	1.52
3	1	1.0	2.0	40		2.0	q/cb	3	3									6.0				B365184	65.53	67.06	**0.107**			VA05082983	1.53
3	1	1.0	2.0	5	60	2.0	q/cb	3	3									12.0				B365185	67.06	68.58	**1.410**			VA05082983	1.52
2	3	0.3	0.6	45		1.0	q/s	3	1									1.0				B365186	68.58	70.10	**0.029**			VA05082983	1.52
2	3	0.3	0.5	30		1.0	cb/q	3	1								5.0					B365187	70.10	71.63	**0.033**			VA05082983	1.53
5	1	1.0	4.5	30	50	2.0	cb/q	3	3									2.0				B365188	71.63	73.15	**0.152**			VA05082983	1.52
5	1	1.0	4.5	30	50	2.0	cb/q	3	3									2.0				B365189	71.63	73.15	**0.113**	PD/CA		VA05082983	1.52
																						B365190	STANDARD 4D		**0.435**	4D		VA05082983	
4	1	1.2	2.4	40	65	2.0	q/cb	3	3								1.0	2.0				B365191	73.15	74.68	**0.270**			VA05082983	1.53
1	1	1.1	1.1	25									2.0																
2	1	1.0	2.0	45		2.0	q	4	4		2.0	1.0	1.0									B365192	74.68	76.20	**0.203**			VA05082983	1.52
							cb	1																					
5	1	0.8	4.8	40	55	2.0	cb/q	3	1	0.1								8.0		0.1		B365193	76.20	77.72	**0.154**			VA05082983	1.52
3	1	4.0	6.0	45	60	4.0	cb/q	5	3									10.0		10.0		B365194	77.72	78.75	**0.156**			VA05082983	1.03
2	6	0.3	0.5	30	50	6.0	q/s/cb	4	5																				
1	1	0.6	0.6	10		2.0	q	4	4		10.0		5.0			0.1						B365195	78.75	79.25	**0.801**			VA05082983	0.50
																						B365196	BLANK		**<0.005**			VA05082983	
7	1	1.0	0.8	40		2.0	q	2	3	0.1	4.0		3.0			0.1		4.0				B365197	79.25	80.50	**0.311**			VA05082983	1.25
3	1	1.0	2.0	30		2.0	q/cb	5	2									4.0		1.0		B365198	80.50	81.19	**4.360**			VA05082983	0.69
3	1	1.0	3.0	55		2.0	q/cb	3	2	0.1								4.0				B365199	81.19	82.30	**0.314**			VA05082983	1.11
2	3	1.2	1.5	45		1.0	q/cb	1	2													B365200	82.30	83.82	**0.131**		NEW SAMPLE SERIES	VA05082983	1.52
3	1	2.0	3.5	55	30	0.5	q	3	3									10.0				B365801	83.82	85.34	**0.393**			VA05082983	1.52
3	1	2.0	3.5	55	30	0.5	q	3	3									10.0				B365802	83.82	85.34	**0.199**	DUP		VA05082983	1.52
5	1	1.0	4.0	50		2.0	q/s	3	2								0.1	3.0				B365803	85.34	86.87	**0.103**			VA05082983	1.53
3	1	1.0	1.6	50	60	2.0	q/cb	3	3								0.1	3.0				B365804	86.87	88.39	**0.178**			VA05082983	1.52
4	1	3.0	6.0	40		2.0	q/cb	4	3								0.1	5.0		1.0		B365805	88.39	89.92	**0.529**			VA05082983	1.53
3	4	0.5	1.3	15		1.0	cb/lim	3	5																				
5	1	0.4	1.7	40	45	1.0	q	3	1		5.0	1.0	2.0					1.0				B365806	89.92	91.44	**0.075**			VA05082983	1.52
4	1	3.0	5.5	40	20	2.0	q/cb	3	3		2.0						1.0	2.0		2.0		B365807	91.44	92.96	**0.077**			VA05082983	1.52
2	1	0.6	1.2	40	5	0.5	q	3	3									0.1				B365808	92.96	94.49	**0.057**			VA05082983	1.53
2	1	0.6	1.2	40	5	0.5	q	3	3									0.1				B365809	92.96	94.49	**0.052**	PD/CA		VA05082983	1.53
																						B365810	STANDARD 7G		**4.330**	7G		VA05082983	
1	1	1.2	1.2	22		1.0	q	3	2				0.1				2.0	5.0				B365811	94.49	96.01	**0.053**			VA05082983	1.52
2	1	1.0	1.5	5		2.0	q/cb	3	1								1.0	1.0		0.1		B365812	96.01	97.54	**0.067**			VA05082983	1.53
4	1	1.0	3.0	20	45	1.0	q	2	4									4.0		0.1		B365813	97.54	98.89	**0.220**			VA05082983	1.35
																						B365814	98.89	100.06	**1.195**			VA05082983	1.17
2	1	0.6	0.9	30		3.0	q/cb	2	5				5.0					0.1				B365815	100.06	100.58	**0.131**			VA05082983	0.52
																						B365816	BLANK		**<0.005**			VA05082983	
7	1	1.0	5.5	40	130	1.0	q/cb	3	3									3.0				B365817	100.58	102.11	**0.885**			VA05082983	1.53
3	4	0.1	0.3	40		2.0	cb	3	1													B365818	102.11	103.63	**0.108**			VA05082983	1.52
1	1	1.0	1.0	20		1.0	q	1	3		0.1	0.1	2.0					1.0											
3	1	1.0	2.5	20			q/cb	3	4									1.0				B365819	103.63	105.16	**0.035**			VA05082983	1.53
2	1	0.3	0.6	1		2.0	lim	5	5									1.0				B365820	105.16	106.68	**2.760**			VA05082983	1.52

DRILL LOG LEGEND P1

DRILL HOLE # :
DG05-309C

DATE: September 1-8, 2005 PAGE 5 of 12

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.35	121.92	GND texture returns to visibility, beneath limonite colouration, still pervasive.	3				1	
10		121.92	127.27	Back to very limonite-rich rock. 75% is opaque, brown and uniform with virtually no sign of GND texture. Sericite dominates the outer edges of these limonitic zones, up to a few cm wide. Coarse carbonate grains are also seen with textured GND zones.	4	2			2	
10		127.27	140.21	Less stained GND. Clear GND separated by selvages (lim around veins and fractures, little throughout GND matrix. Veins and veinlets are easily distinguished but most appear lim-stained and rearranged, i.e. bent or sheared. Only one carbonate vein is pristine white and un-moved. Limonite is carb-rich.	3			1	2	
10		140.32	158.50	GND with zones of variable lim-staining (oxidation) and carbonate. To 143.25m, surrounding bent, low-angle qtz veins is opaque light brown alteration in GND, to greenish grey GND with 2-4mm coarse grains of lim-stained carbonate. From 143.25 to 145.0m is 80% unalt'd, 'blue' GND. 20% is qtz veins w/ moderate mineralization and small qtz selvages, as well as a few thin carbonate/lim veinlets with relatively wide selvages. These vein types continue throughout section, with variable frequency, but usually 2-4 per metre. Zone of brecciated, sandy, lim-covered pebbles from 151.2 to 151.6m, with some loss of recovery here. Large selvages around fractures: 4cm+ 'chunky' carbonate within lim as above. Outer selvage (2cm+) is moderately silicified and has minor sericite. At 156.75 to 157.75m, evidence of shear appears - foliation development (at ≥50° to CA) and increase in clay minerals. GND's	3	1		1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6	20														2.0				B365821	106.68	108.20	**1.665**			VA05082983	1.52
3	1	0.2	0.6	20														2.0				B365822	106.68	108.20	**3.400**	DUP		VA05082983	1.52
																						B365823	108.20	109.73	**0.118**			VA05082983	1.53
1	1	1.0	1.0	45														4.0				B365824	109.73	111.25	**0.046**			VA05082983	1.52
3	1	1.0	2.1	50														3.0				B365825	111.25	112.77	**0.043**			VA05082983	1.52
1	1	0.5	0.5	40														2.0				B365826	112.77	114.30	**0.134**			VA05082983	1.53
1	6	0.2	0.2	45		8.0	q/s/cb	5	2									100.0											
2	1	0.6	1.0	40	55													6.0				B365827	114.30	115.82	**0.049**			VA05085049	1.52
1	3	1.0	1.0	40		20.0	q/s	4	5																				
4	1	1.0	3.0	45													0.1	1.0				B365828	115.82	117.35	**0.197**			VA05085049	1.53
4	1	1.0	3.0	45													0.1	1.0				B365829	115.82	117.35	**0.207**	PD/CA		VA05085049	1.53
																						B365830	STANDARD 3C		**0.092**	3C		VA05085049	
2	1	1.0	1.6	40	50	2.0	q	3	3		0.1	0.1	2.0				1.0	3.0				B365831	117.35	117.95	**0.207**			VA05085049	0.60
3	1	0.5	1.5	45														8.0				B365832	117.95	119.03	**0.108**			VA05085049	1.08
1	1	1.0	1.0	50									0.1					2.0				B365833	119.03	120.40	**0.411**			VA05085049	1.37
3	1	0.5	1.5	45	20													2.0				B365834	120.40	121.92	**0.233**			VA05085049	1.52
3	1	0.5	1.5	35	20	4.0	cb/q	3	5	1.0								6.0				B365835	121.92	123.44	**0.350**			VA05085049	1.52
																						B365836	BLANK		**<0.005**			VA05085049	
3	1	1.0	1.8	40		4.0	cb/q	4	4				0.1		0.1			4.0				B365837	123.44	124.97	**0.734**			VA05085049	1.53
4	1	1.0	3.5	25	40	8.0	cb/s	4	4									1.0				B365838	124.97	126.49	**0.201**			VA05085049	1.52
2	1	1.0	2.0	40	30	3.0	cb/s	3	3				0.1		1.0			3.0				B365839	126.49	127.27	**0.347**			VA05085049	0.78
2	4	1.5	2.0	20	35	12.0	cb	3	5																				
3	1	1.0	3.0	20									1.0		1.0			1.0				B365840	127.27	128.68	**0.054**			VA05085049	1.41
1	4	0.6	0.6	35		6.0	cb/s	3	4									0.1											
2	1	1.0	2.0	40	20	3.0	q/cb	3	2						2.0			1.0				B365841	128.68	129.54	**0.205**			VA05085049	0.86
2	1	1.0	2.0	40	20	3.0	q/cb	3	2						2.0			1.0				B365842	128.68	129.54	**1.475**	DUP		VA05085049	0.86
4	1	1.0	3.6	45		2.0	cb/q	2	3						1.0			1.0				B365843	129.54	131.07	**0.293**			VA05085049	1.53
1	4	0.5	0.5	25		2.0	cb/q	3	4																				
3	1	2.0	4.0	30		1.0	q	2										1.0				B365844	131.07	132.59	**0.060**			VA05085049	1.52
2	1	0.5	1.0	35		2.0	q/cb/s	2	2									2.0				B365845	132.59	134.12	**0.051**			VA05085049	1.53
5	1	0.5	2.5	40	25	3.0	q/cb/s	3	2		2.0				4.0			2.0				B365846	134.12	135.64	**0.134**			VA05085049	1.52
4	1	1.1	3.5	30		2.0	q/s/cb	2	3				2.0		3.0							B365847	135.64	137.16	**0.181**			VA05085049	1.52
4	1	1.0	3.5	45		2.0	q/s/cb	3	1		2.0				1.0							B365848	137.16	138.68	**5.460**			VA05085049	1.52
4	1	1.0	3.5	45		2.0	q/s/cb	3	1		2.0				1.0							B365849	137.16	138.68	**5.160**	PD/CA		VA05085049	1.52
																						B365850	STANDARD 7G		**4.570**	7G		VA05085049	
7	1	1.0	6.0	30	20	2.0	q	4	1		3.0		1.0					2.0				B365851	138.68	140.21	**1.135**			VA05085049	1.53
							cb/s	1																					
6	1	1.0	5.2	40	160	4.0	q	4	2													B365852	140.21	141.73	**0.723**			VA05085049	1.52
1	4	0.5	0.5	25																									
1	4	0.4	0.4	160														10.0											
2	1	2.0	3.0	30		2.0	q	3	1		2.0		1.0									B365853	141.73	143.25	**0.423**			VA05085049	1.52
3	1	1.0	3.0	40		1.0	q	2	1		1.0		0.1									B365854	143.25	144.78	**0.163**			VA05085049	1.53
3	1	0.5	1.5	40		1.0	q	3	1		1.0							2.0				B365855	144.78	146.31	**0.589**			VA05085049	1.53
1	4	0.3	0.3	50		8.0	cb/s/q	3	2																				
																						B365856	BLANK		**<0.005**			VA05085049	
3	1	0.5	1.5	45		2.0	q	2	4		1.0							1.0				B365857	146.31	147.83	**0.836**			VA05085049	1.52
4	1	0.5	2.0	50	20	1.0	q/s	3	1		1.0						1.0	0.1				B365858	147.83	149.35	**0.163**			VA05085049	1.52
3	4	0.2	0.6	40		12.0	cb/s	4	3									1.0											
3	1	1.0	2.6	40	20	1.0	q	3										2.0				B365859	149.35	150.88	**0.381**			VA05085049	1.53
2	1	0.5	1.0	45	20	0.5	q	3	1									4.0		2.0		B365860	150.88	152.40	**0.063**			VA05085049	1.52
																						B365861	152.40	153.92	**0.726**			VA05085049	1.52

DRILL LOG LEGEND P1	DATE: September 1-8, 2006	PAGE 7 of 12	
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		158.50	159.42	Fault zone's focus. All fine-grained gouge except general line of (usually) broken qtz veins. Clay-rich (30%), and colourful - yellow, orangey brown, blue green, for 40cm. Granular texture reappears at 159.2m.	4	3		3	3	
10		159.42	163.07	GND texture here - ~20% unox'd, unalt'd, weak from numerous lim fract in-fills. Qtz veins still not complete.	3				1	
10		163.07	164.59	Carb-clay veins at 25° and 135° to CA through sericitic/ opaque lim'd brown rock, very weak and crumbly.	4	3		3	5	
10		164.59	181.36	Unalt'd, competent GND except surrounding qtz, qtz/carb and carb veins. Mineralization is good. VG seen associated with pyrite, also significant aspy and po. Minor limonite and carbonate. Sericite appears in selvages more strongly toward middle-end of section. Scorodite seen (bright blue-green) in one vein and selvage.	2	2			1	
10		181.36	185.94	Sericitic alteration pervasive here. Limonite and oxidation confined to veinlets and minor within selvages, minor through matrix, last metre of section. Good mineralization. One sulphide vein at 182.4m contains 1-2mm euhedral pyrite, ox'd and un-ox'd	1	1			1	
10		185.94	202.69	From 185.94 to 191.27m, rock is unalt'd GND except selvages surrounding qtz veins ± carbonate. At 191.27m, zone of extreme alt'n begins with massive sulphide veins to 192.50m. After this alt'd section, rock is competent and unalt'd except silicified and ser'd selvages surrounding qtz veins. One carb/ser-covered fracture breaks core in half at 0° to CA from 194.5 to 195.0m. No evidence of motion here.	1					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval					
						Selvages				Sulphides									Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B365862	152.40	153.92	**0.199**	DUP		VA05085049	1.52
3	1	1.0	2.8	40		2.0	q/s	2										4.0				B365863	153.92	155.45	**0.271**			VA05085049	1.53
2	3	1.0	1.5	60	30	6.0	q/cb	3	4									0.1											
							s	2																					
2	1	1.0	1.5	40		1.0	q	4	2									1.0				B365864	155.45	156.97	**0.926**			VA05085049	1.52
2	4	2.0	3.0	70		2.0	cb/s	4	2									4.0											
1	1	1.2	1.2	10							2.0						1.0					B365865	156.97	158.50	**0.063**			VA05085049	1.53
4	1	1.0	3.0	20														1.0				B365866	158.50	159.42	**0.458**			VA05085049	0.92
3	1	1.0	2.5	50							0.1									1.0		B365867	159.42	160.02	**0.037**			VA05085049	0.60
1	1	0.4	0.4	60		0.5	cb	2	2									0.1				B365868	160.02	161.55	**0.080**			VA05085049	1.53
1	1	0.4	0.4	60		0.5	cb	2	2									0.1				B365869	160.02	161.55	**0.098**	PD/CA		VA05085049	1.53
																						B365870	STANDARD 1A		**0.880**	1A		VA05085049	
2	1	1.0	1.5	50		2.0	q/cb	5	2		0.1									2.0		B365871	161.55	163.07	**0.245**			VA05085049	1.52
2	1	1.0	2.0	50	35																	B365872	163.07	164.59	**0.099**			VA05085049	1.52
3	4	1.0	3.0	45	150		s/cb	5	4									0.1											
4	1	3.0	7.0	45		2.0	q/cb	4	3	3.0	2.0							2.0				B365873	164.59	166.12	**1.040**			VA05085049	1.53
3	1	1.0	2.5	40		0.5	q	3	1		2.0							0.1				B365874	166.12	167.65	**0.111**			VA05085049	1.53
							s	1																					
5	1	4.0	8.0	40		1.0	q/cb	3		5.0			2.0					5.0				B365875	167.65	169.16	**1.770**			VA05085049	1.51
3	3	1.2	2.4	50		30.0	cb/s	4	1																				
																						B365876	BLANK		**<0.005**			VA05085049	
5	1	2.0	6.0	30	50	1.0	2	q											8.0			B365877	169.16	170.68	**0.949**			VA05085049	1.52
3	4	1.0	2.0	60		10.0	cb/s	3	1																				
6	1	5.0	9.0	35	60	4.0	q	3	1	5.0						1.0						B365878	170.68	172.21	**5.360**			VA05085049	1.53
1	3	0.5	0.5	35		1.0	q/cb	3	2									4.0											
4	1	4.0	6.0	50		2.0	q	3		3.0	5.0	0.1	0.1					2.0				B365879	172.21	173.74	**0.551**			VA05085049	1.53
							cb/s	2	1																				
6	1	1.0	5.0	45		2.0	q/s	3	1		4.0		2.0			0.1		2.0				B365880	173.74	175.26	**12.650**			VA05085049	1.52
							cb	1																					
6	1	1.0	4.5	35	40	2.0	q/s	3	1		2.0		0.1					5.0				B365881	175.26	176.79	**0.703**			VA05085049	1.53
6	1	1.0	4.5	35	40	2.0	q/s	3	1		2.0		0.1					5.0				B365882	175.26	176.79	**0.662**	DUP		VA05085049	1.53
5	1	6.0	10.5	50		2.0	q/cb/s	3	1	3.0								1.0				B365883	176.79	178.31	**1.255**			VA05085049	1.52
4	1	3.0	6.5	40	60	6.0	q/s	3	1		0.1		0.1					4.0				B365884	178.31	179.83	**0.967**			VA05085049	1.52
6	1	2.5	7.5	30	60	4.0	q/s	3	1		1.0		0.1				2.0					B365885	179.83	181.36	**1.410**			VA05085049	1.53
							cb	1																					
5	1	1.2	4.0	60		4.0	q/s	3			1.0											B365886	181.36	182.12	**7.230**			VA05085049	0.76
							cb	1																					
1	1	1.0	1.0	40		6.0	q/s/cb	4	1	3.0	3.0							1.0				B365887	182.12	182.88	**0.783**			VA05085049	0.76
1	6	6.0	6.0	40		40.0	q/cb/s	4	1	40.0	0.1							50.0											
4	1	1.2	3.5	60			s/cb	4	1	1.0	0.1					1.0		1.0				B365888	182.88	184.40	**1.890**			VA05085049	1.52
3	3	1.0	2.5	60	40		q/cb	4	1							2.0		3.0											
3	3	1.0	2.5	60	40		q/cb	4	1							2.0		3.0				B365889	182.88	184.40	**1.695**	PD/CA		VA05085049	1.52
																						B365890	STANDARD 5E		**1.425**	5E		VA05085049	
3	1	1.0	2.7	60	40	20.0	q/s	3	2									0.1				B365891	184.40	185.94	**0.554**			VA05085049	1.54
							cb	1																					
3	1	1.5	2.5	35	70	1.0	q	3										0.1				B365892	185.94	187.45	**0.958**			VA05085049	1.51
4	1	0.5	2.0	50		6.0	q/s	4	1	8.0			0.1					4.0				B365893	187.45	188.98	**0.250**			VA05085049	1.53
3	1	1.0	3.0	45		2.0	cb/q/s	4			2.0	0.1	2.0							1.0		B365894	188.98	190.50	**0.259**			VA05085049	1.52
1	3	4.0	4.0	60		4.0	cb/s	4	1	0.1	5.0		0.1																
2	1	0.5	1.0	50		1.0	q	3	1											3.0		B365895	190.50	191.27	**0.488**			VA05085049	0.77
1	3	0.2	0.2	40		6.0	cb/s	3	1									5.0											
																						B365896	BLANK		**<0.005**			VA05085049	
2	1	1.0	1.5	70		4.0	cb/q	1	1	10.0								20.0				B365897	191.27	192.02	**0.156**			VA05085049	0.75
3	6	1.5	3.5	40			s/cb	4	2	60.0			2.0					38.0											
1	3	0.4	0.4	50														5.0											
6	1	1.0	4.0	50	70	2.0	q/s	3	1	0.1								4.0				B365898	192.02	193.55	**0.372**			VA05085049	1.53

DRILL LOG LEGEND P1	DATE: September 1-8, 2005	PAGE 4 of 12	
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		202.69	207.27	60% strongly alt'd with carb and ser. All alt'n associated with qtz, qtz/carb, and carb veins. Minor limonite on randomly-oriented fractures and within selvages. One 8cm zone of carb-rich (+ser) clay at 205.86m, associated with black clay veinlet (ox'd py?).	1	3		1	2	
10		207.27	225.54	Sheeted qtz veins with small qtz/ser/carb selvages. Mineralization is variable from vein to vein - some have up to 10% sulphides (including scor, bt, and ox'd), while others have <1%. Selvages increase in intensity and sericitic and carbonitic alteration and size toward middle of section.	1	2			2	
10		225.54	262.13	Competent, unalt'd GND with excellent recovery. Sheeted qtz veins (grey qtz). Very little breakage - common 5 foot lengths of core. Breaks are at zones of weakness (carb-rich veins, concentrations of veins, or within selvage material). Breaks are few. Selvage material blends into surrounding medium-to-coarse grained GND texture. Scor. conc at boundaries to veins; po exposed on rough breakage faces - pale silvery bronze - metallic lustre. Appears 'flattened' over qtz, etc). Slight carb increase from 247.40 to 248.60m and loss of recovery; weakness: slickensides in po - metallic, mod'ly ox'd into carb clay which is also slickensided - no vein assoc on face at 50° to CA. Nearby vein at 50°; Selvages increase in intensity with increased sulphide content in vein and at margins in selvages; Carbonate-sand and brecciated GND contacts competent GND @ 30° to CA @ 262.0m, crumbly and weak foliation for ~1m; Fractures have no selvages but fracture faces show a thin film of clay/carb and one face has ~80% coverage of po and minor aspy with no associated vein; Fresh and subhedral		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Sulphides				Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							cb	1																	B365899	193.55	195.08	1.940			VA05085049	1.53
4	1	1.0	4.0	55	35	1.0	q	3			1.0							1.0													
1	1	1.0	1.0	60		6.0	q/cb	5		1.0	2.0							1.0		2.0											
2	3	1.0	2.0	60		10.0	q/cb/s	5										1.0													
5	1	1.0	4.0	40		3.0	q/s	4			4.0		1.0				0.1	0.1				B365900	195.08	196.60	1.360			VA05085049	1.52
5	1	2.0	5.5	55	40	2.0	q/s	3			5.0		1.0					4.0				B365901	196.60	198.11	0.279			VA05085049	1.51
5	1	2.0	5.5	55	40	2.0	q/s	3			5.0		1.0					4.0				B365902	196.60	198.11	0.880	DUP		VA05085049	1.51
2	1	1.0	2.0	70														2.0				B365903	198.11	199.64	0.747			VA05085049	1.53
4	1	1.0	5.0	65		1.0	q	3	2		2.0				1.0			0.1				B365904	199.64	201.17	0.090			VA05085049	1.53
1	4	1.0	1.0	50		20.0	q/s	4	2									0.1													
							cb	2																							
7	1	1.0	5.5	40	55	4.0	q	4	1		4.0							1.0		0.1		B365905	201.17	202.69	0.108			VA05085049	1.52
							s/cb	1																							
4	1	2.0	5.0	50	80	20.0	q/s	4			2.0		0.1					1.0				B365906	202.69	204.21	0.877			VA05085049	1.52
2	3	1.0	2.0	30	60	10.0	cb/s	5	1									4.0													
4	1	1.0	3.0	50	60					1.0								0.1				B365907	204.21	205.74	0.257			VA05085049	1.53
2	3	1.0	2.0	30	70													5.0													
5	1	1.2	3.5	60	20	40.0	q/s	4		0.1								2.0				B365908	205.74	207.27	0.295			VA05085049	1.53
							cb	1	1																						
5	1	1.2	3.5	60	20	40.0	q/s	4		0.1								2.0				B365909	205.74	207.27	0.288	PD/CA		VA05085049	1.53
																						B365910	STANDARD 4D		0.445	4D		VA05085049	
6	1	4.0	12.0	50	30	3.0	q	2		0.1	0.1				2.0		1.0	2.0	1.0			B365911	207.27	208.74	1.805			VA05085049	1.47
5	1	1.0	4.5	40	60	2.0	q/s	3	1		7.0		0.1									B365912	208.74	210.30	1.150			VA05085049	1.56
3	1	0.6	1.4	40	60	1.0	q/s	3	1		2.0											B365913	210.30	211.84	0.380			VA05085049	1.54
9	1	1.3	6.5	50		2.0	q/s/cb	4	1	0.1	3.0		0.1						1.0	0.1		B365914	211.84	213.36	0.354			VA05085049	1.52
7	1	1.0	4.5	50		2.0	q/cb	4	1		1.0		1.0					1.0	2.0			B365915	213.36	214.88	0.950			VA05085049	1.52
																						B365916	BLANK		<0.005			VA05085049	
2	4	1.0	1.5	60		20.0	cb/s	3		0.1	0.1							3.0				B365917	214.88	216.40	0.425			VA05085049	1.52
4	1	1.5	4.0	40	50	3.0	q/s	4										5.0													
							cb	1																							
8	1	1.0	7.0	30	60	4.0	q/s	3			3.0							0.1				B365918	216.40	217.95	0.466			VA05085049	1.55
5	1	4.0	7.5	60	25	20.0	q/cb/s	5			5.0		1.0				0.1	0.1	2.0	1.0		B365919	217.95	219.45	0.628			VA05085049	1.50
5	1	1.0	4.0	60	45	30.0	q/s/cb	5	1		2.0				0.1			0.1	2.0	2.0		B365920	219.45	220.98	1.330			VA05085049	1.53
3	1	2.0	4.0	40		4.0	q	4	1	2.0								0.1				B365921	220.98	222.50	1.140			VA05085049	1.52
3	3	0.7	2.0	30		10.0	cb/s	5	1									2.0													
3	1	2.0	4.0	40		4.0	q	4	1	2.0								0.1				B365922	220.98	222.50	0.660	DUP		VA05085049	1.52
3	3	0.7	2.0	30		10.0	cb/s	5	1									2.0													
5	1	1.0	3.5	45		1.0	q	3														B365923	222.50	224.03	0.465			VA05085049	1.53
							s	1																							
3	3	1.0	2.5	50	30	8.0	cb/s	4			4.0						0.1	3.0													
7	1	1.2	8.0	45		2.0	q/s	3			1.0							0.1	2.0	2.0		B365924	224.03	225.54	0.159			VA05085049	1.51
							cb	2	2																						
5	1	1.0	3.0	60		20.0	cb/s	4	3		1.0							1.0				B365925	225.54	227.08	0.176			VA05085049	1.54
4	1	2.5	5.0	50		2.0	q	4	1		3.0							2.0	1.0	3.0		B365926	227.08	228.60	0.219			VA05085049	1.52
5	1	1.0	4.0	50		2.0	q	4			4.0											B365927	228.60	230.12	0.213			VA05085049	1.52
							cb/s	1																							
6	1	1.0	6.0	40	55	6.0	q/cb/s	4			6.0	0.1	1.0					1.0	5.0			B365928	230.12	231.65	0.185			VA05085049	1.53
6	1	1.0	6.0	40	55	6.0	q/cb/s	4			6.0	0.1	1.0					1.0	5.0			B365929	230.12	231.65	0.217	PD/CA		VA05085049	1.53
																						B365930	STANDARD 7G		4.550	7G		VA05085049	
4	1	0.5	2.0	50		2.0	q/cb	2														B365931	231.65	233.17	0.386			VA05085049	1.52
							s	1																							
7	1	1.0	5.5	50		2.0	q/s	4			2.0		0.1						5.0	0.1		B365932	233.17	234.70	0.241			VA05085049	1.53
6	1	1.0	5.5	60		4.0	cb/s	3			3.0		1.0					3.0				B365933	234.70	236.22	1.040			VA05085049	1.52

DRILL LOG LEGEND P1	DATE: September 1-8, 2005	PAGE 11 of 12	
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		262.13	271.28	More carb-rich GND. Breakage into <10cm lengths, random fracture orientations (see tech sheets). Still, good recovery overall. Carb concentrated in selvages further into section: @266.75 - 271.28m. Max selvages noted on next page. Last sample high carb and ser - grades into next section. Strong slickensides on low angle (~10° to CA) frac faces @270m.	1	2			2	
10		271.28	274.62	GND: Strong slickensides noted in low angle fractures continue. Increase in carb + ser alt'n to EOH - selvages often indistinguishable from one another.		2			3	

DRILL LOG LEGEND — P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

PAGE 12 of 12


094876

Selvage Alteration: ohl = chlorite, k = K-spar, s = sericite, q = quartz/silica, ob = carbonate, b = biotite, oc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval					
						Selvages				Sulphides								Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
6	1	1.0	3.0	45	30	3.0	q/s	4			5.0		2.0						2.0	1.0		B365934	236.22	237.75	**0.568**			VA05085049	1.53
6	1	35.0	9.0	50		2.0	q	4			2.0		1.0							1.0		B365935	237.75	239.27	**0.423**			VA05085049	1.52
							cb/s	2																					
																						B365936	BLANK		**<0.005**			VA05085049	
6	1	3.0	6.0	50	35	1.0	q	4	0		2.0							1.0	5.0			B365937	239.27	240.80	**1.125**			VA05085049	1.53
8	1	0.5	4.0	50	80	4.0	q	4			0.1								5.0	1.0		B365938	240.80	242.32	**0.288**			VA05085049	1.52
8	1	1.0	5.0	60		3.0	q/s	4			1.0									2.0		B365939	242.32	243.85	**0.315**			VA05085049	1.53
5	1	2.0	4.0	50	20	4.0	q/s/cb	5	0		5.0	0.1	3.0					3.0				B365940	243.85	245.36	**0.243**			VA05085049	1.51
4	1	1.0	3.0	45		28.0	q/cb	5			10.0								5.0	1.0		B365941	245.36	246.89	**0.117**			VA05085049	1.53
4	1	1.0	3.0	45		28.0	q/cb	5			10.0								5.0	1.0		B365942	245.36	246.89	**1.080**	DUP		VA05085049	1.53
3	1	1.0	3.0	50		4.0	q/s	3	0		1.0									0.1		B365943	246.89	248.41	**0.456**			VA05085049	1.52
5	1	1.0	5.0	60		1.0	q	4	0		1.0							10.0	5.0			B365944	248.41	249.94	**0.290**			VA05085049	1.53
6	1	1.5	6.0			2.0	q	4			2.0								4.0			B365945	249.94	251.46	**0.255**			VA05085049	1.52
5	1	1.0	5.0	50		4.0	s/q	3			0.1	0.1							6.0			B365946	251.46	252.99	**0.097**			VA05085049	1.53
4	1	1.0	4.0	50		2.0	q/s	3											2.0			B365947	252.99	254.51	**0.282**			VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365948	254.51	256.03	**0.261**			VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365949	254.51	256.03	**0.493**	PD/CA		VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365950	STANDARD 2B		**2.970**	2B		VA05085049	
6	1	2.0	5.0	45		6.0	cb/s	4	1		3.0	1.0							3.0			B365951	256.03	257.56	**0.169**			VA05085049	1.53
8	1	1.0	7.0	40	55	4.0	q/s	3		1.0	1.0								2.0	0.1		B365952	257.56	259.09	**1.330**			VA05085049	1.53
1	1	0.5	0.5	60		1.0	q/s	3			1.0											B365953	259.09	260.60	**0.025**			VA05085049	1.51
4	1	0.5	2.0	60		2.0	q/s	5	0									tr				B365954	260.60	262.13	**0.100**			VA05085049	1.53
3	1	1.0	3.0	40		4.0	q	3	0		3.0								1.0	2.0		B365955	262.13	263.65	**0.066**			VA05085049	1.52
																						B365956	BLANK		**<0.005**			VA05085049	
2	1	1.0	2.0	50		10.0	q/s	4			2.0						1.0					B365957	263.65	265.17	**0.124**		musc. Or moly diss. In selvage	VA05085049	1.52
3	1	1.0	3.0	45		40.0	bc/s	4		8.0								1.0				B365958	265.17	266.70	**0.119**		massive py also in veinlets w/in 1cm of qtz vein	VA05085049	1.53
2	1	1.0	2.0	65		3.0	cb/q	4			1.0		2.0					2.0	6.0			B365959	266.70	268.23	**0.062**			VA05085049	1.53
3	1	1.0	2.0	50		3.0	q/s	5			4.0							1.0				B365960	268.23	269.75	**0.063**			VA05085049	1.52
							cb	2																					
4	1	1.0	4.0	30	60	8.0	s/cb	4			2.0											B365961	269.75	271.28	**0.036**			VA05085049	1.53
4	1	1.0	4.0	30	60	8.0	s/cb	4			2.0											B365962	269.75	271.28	**0.075**	DUP		VA05085049	1.53
1	6	1.0	1.0	35		30.0	c/b	4		5.0								90.0				B365963	271.28	272.80	**0.042**		numerous carb veinlets	VA05085049	1.52
1	1	1.0	1.0	35			s/q	2																					
2	1	1.5	1.0	70		1.0	q	5		3.0										2.0		B365964	272.80	274.62	**0.139**		10%clay min (white) + carb.	VA05085049	1.82
2	6	1.0	1.5	50		40.0	cb	5										90.0											
																							EOH						

094870



APPENDIX F

Dublin Gulch 2005 Diamond Drill Logs

094876

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-276C

PROJECT: Dublin Gulch - 1735

DATE STARTED: 23-May-05	DATE COMPLETED: 27-May-05
LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead	
CONTRACTOR: Britton Brothers	

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 12.19m
Deviation:
Casing: 21.94m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

FROM	TO	LITHOLOGY
12.19m	258.0m	GND

FROM	TO	ALTERATION
45m	65m	ox, ser, chl, arg
87m	100m	ox, ser, chl, arg, cb
113m	135m	ox, ser, chl, arg, cb
230m	250m	ox, ser, chl, arg, cb

FROM	TO	MINERALIZATION (Veins)
105m	160m	pyrite, pyrrhotite, arsenopyrite, minor chalcopyrite
185m	258m	

GROUND ELEVATION: 1039m

BEARING: 000	DIP: -50°
COORD SYSTEM: NAD 27:	EASTING: 459744 NORTHING: 7099236
COORD SYSTEM: NAD 83:	EASTING: 459624 NORTHING: 7099420
NAD 27 (CORRECTED for historic grid):	EASTING: 459714 NORTHING: 7099246
SECTION LINE 459714E (historic grid)	

SAMPLING DETAILS

Sample Sequence: B291001 to B291113
Requisition #: MASP448STRGOL.05Q — Date Shipped: 26-May-05
Lab Record #: VA05042605 — Date Received: 1-June-05
Sample Sequence: B2910114 to B291298
Requisition #: MASP448STRGOL.05Q — Date Shipped: 2-June-05
Lab Record #: VA05045435 — Date Received: 15-June-05

Duplicates:	B291002, B291022, B291042, B291062, B291082, B291102, B291122, B291142, B291162, B291182, B291202, B291222, B291242, B291262, B291282
Preparation Duplicate/ Check Assay:	B291009, B291029, B291049, B291069, B291089, B291109, B291129, B291149, B291169, B291189, B291209, B291229, B291249, B291269, B291289
Standards:	B291010(3C), B291030(3C), B291050(3C), B291070(3C), B291090(3C), B291110(2B), B291130(4D), B291150(4D), B291170(4D), B291190(3C), B291210(2B), B291230(4D), B291250(4D), B291270(5E), B291290(1A)
Blanks:	B291016, B291036, B291056, B291076, B291096, B291116, B291136, B291156, B291176, B291196, B291216, B291236, B291256, B291276, B291296

SURVEYS:

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (Corr + 27)	AZ (Corr + 26)
50	333	50.8	000	359
100	332.5	51.2	359.5	358.5
200	332.9	51.3	359.9	358.9
260	334.9	50.4	001.9	000.9

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 1 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-12.19			Casing - no core recovery						
10	12.19-258.00	12.19	14.59	GND (Main interval). GND is limonite stained. Core is extremely broken to grav/sand. Recovery is poor. GND has pervasive limonite in fracs and appears partially decomposed. Mineralogical characteristics include: 40% qtz, 30% hornblende, 20% biotite, 10% limonite & qtz veins				1		
10		14.59	15.24	Fault gouge unit. Limonite pervasive within grey gouge/crumbly brecciated GND with visible qtz eyes. Possible hydrothermally altered GND. Preferable interpretation is hyd. altered GND, within physically decomposed core.	1	1		3		1
10		15.24	17.49	Broken GND (gravel size to sandy clay). Note: poor core recovery, extensive limonite	2		1			4
10		17.49	17.70	Clay gouge fault zone. Core contains extensive predominant clay with visible quartz eyes, pieces of gravel-sized GND, essentially decomposed GND (hydrothermally alt'd) as from 14.59-15.24m.	1	1		4		1
10		18.29	20.88	Extremely poor core recovery (~20%). Round, gravel-sized GND.						
10		20.88	21.34	Core coherency is of sugary gravel; limonite coated pieces. Minor sericite, no visible sulphides.						
10		21.34	25.58	Qtz vn @ 22.63m; 30 degrees to CA, tr aspy dissem, ~0.5cm thick. Trace dissem pyrite @ ~23.26m w/in the GND, no obvious vns in area.						
10		25.58	25.91	GND becomes extremely broken to gravel/sand sizes. Pieces of qtz vns visible; no sulphides or structure observable. Heavy limonite staining.	1			1		1
10		25.91	30.48	Core is becoming more competent. Avg frac angles are ranging from 30-40° to CA. Limonite staining abundant & pervasive on frac srfc's; Qtz vn @ ~26.0m @ 70° to CA. qtz was cloudy grey w/ no visible dissem sulphides.	1					
10		30.48	32.35	Qtz vn @ ~30.60m @ 70° to CA, no visible sulphides, milky translucent color. Qtz vn @ ~30.82m @ 70° to CA, translucent milky qtz.						
10		32.35	33.03	V.broken core due to hydrothermal alt'n. Sugary core w/ minor clay (10%), abundant limonite staining. Minor qtz pc's indicate minor vning.	1			1		
10		34.02	34.90	Same as above only more abundant gravel sized pc's and less qtz vn chips.						
10		35.15	35.50	Milky & clear qtz vn @ 35.21m parallel to CA. No visible sulphides inclusive. A microvnlet @ ~45° to CA x-cutting the vn contained a few dissem aspy.	1					
10		36.56	36.58	Qtz vn @ 40-45° to CA. proximally w/in 5-8cm dissem aspy is present.						
10		37.55	39.62	Alt'd section of GND, extensively fractured. Abundant limonite pervasive & on fracs. Gravel/sand/clay consistency. Qtz pebbles observed indicating vning.	1			1		
10		39.62	41.10	Milky qtz vn @ 41.10m w/ dissem aspy @ 40° to CA. Surrounding 10cm on either side of vn have endured sericite alt'n & have pervasive limonite staining.	1					
10		41.10	42.55	Core is broken but displays qtz vning, which appears to have aided in decomposition of GND. Minor visible sericite (1-2%), pervasive limonite & on fracs. Minor dissem aspy & minor vugging w/in qtz vn pc's.	1	1		1		

094876

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																					lim	B291001	12.19	13.72	0.013		VA05042605	1.53	
																						B291002	12.19	13.72	0.107	DUP	VA05042605	1.53	
																						B291003	13.72	15.24	0.521		VA05042605	1.52	
																						B291004	15.24	16.76	0.024		VA05042605	1.52	0.338
																						B291005	16.76	17.49	0.079		VA05042605	0.73	1.305
																						B291006	17.49	17.70	0.164		VA05042605	0.21	
																						B291007	17.70	18.29	0.009		VA05042605	0.59	
																						B291008	18.29	19.81	0.018		VA05042605	1.52	0.329
																						B291009	18.29	19.81	0.018	PD/CA	VA05042605	1.52	
																						B291010	STANDARD 3C		0.081	3C	VA05042605		
																						B291011	19.81	20.88	2.400		VA05042605	1.07	0.34
																						B291012	20.88	21.34	0.111		VA05042605	0.46	
1	1	0.5	0.5	30									0.1									B291013	21.34	22.86	0.133		VA05042605	1.52	1.06
																						B291014	22.86	24.38	0.089		VA05042605	1.52	0.579
																						B291015	24.38	25.91	0.059		VA05042605	1.53	0.628
																						B291016	BLANK		<0.005		VA05042605		
1	1	0.25	0.25	70																		B291017	25.91	27.43	0.019		VA05042605	1.52	0.214
																						B291018	27.43	28.96	0.056		VA05042605	1.53	
																						B291019	28.96	30.48	0.034		VA05042605	1.52	
2	1	1	2	70																		B291020	30.48	32.00	0.073		VA05042605	1.52	
																						B291021	32.00	32.35	0.060		VA05042605	0.35	
																						B291022	32.00	32.35	0.090	DUP	VA05042605	0.35	
																						B291023	32.35	33.03	0.074		VA05042605	0.68	
																						B291024	33.03	35.05	0.229		VA05042605	2.02	
1	1	1.0	1.0	45									0.1					1				B291025	35.05	36.58	0.049		VA05042605	1.53	
1	1	2.0	2.0	40	45								0.1					1											
1		2.0											0.1					1				B291026	36.58	37.55	0.106		VA05042605	0.97	
																						B291027	37.55	38.10	0.072		VA05042605	0.55	
																						B291028	38.10	39.62	0.121		VA05042605	1.52	0.36
																						B291029	38.10	39.62	0.130	PD/CA	VA05042605	1.52	
																						B291030	STANDARD 3C		0.089	3C	VA05042605		
1	1	0.5	0.5										0.1					1				B291031	39.62	41.16	0.400		VA05042605	1.54	0.294
																						B291032	41.16	42.65	0.265		VA05042605	1.49	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 3 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		42.80	44.20	Extremely broken GND w/ heavy limonite staining. Some minor qtz pc's indicating vns present but no other info obtainable. Core varies from gravel size to sand to clay (predom sandy gravel).	1			1		5
10		44.20	44.93	25% qtz, 30% k-sp, 10% hbl, 30% bt & 5% other, incl. sulphides. Hydrothermal alt'n across numerous 1mm weathered vns throughout section. Granular limonite covers fractured srfc's. 97% core recovery; core broken into blocks up to 10cm long.	4			1	2	
10		44.93	45.72	1-2mm pyrite grains present w/ intense hydrothermal alt'n; ox'd to siderite on frac srfc's.	3	1		1	2	
10		45.72	46.22	Minor hematite noted, subhedral grains oxidized to bright red. Tiny carb vns, calc & siderite angles indistinguishable as vns are pervasive. Core is gouge to chunks ~6cm in diam.	4			2	2	
10		46.22	47.92	GND varies in degree of breakage from gouge to 15cm solid chunks. Fracs more reg @ 20° angle.	3			2	1	
10		47.92	48.77	Material shows remnants of GND (qtz eyes, bt) but is predom. gouged. Biotite alt'd to v. hard, black mineral. Minor (10%) calcite in frac dominated by limonite.	4			3	2	
10		48.77	49.50	Broken core into ~5cm diam chunks avg, w/ little alt'n except from 49.0-49.2m - gouge zone.	1			3	1	
10		49.50	49.80	Qtz vn seen surrounded by ~10cm pervasively alt'd GND. Ser, aspy noted dissem w/in, as well as limonite. Weakened GND.	1	1			1	
10		49.80	50.29	Broken core. Gouge section 50.7-50.8m. Limonite on fracs, 1mm diam w/ minor calc.	2			1	1	
10		50.29	51.82	GND: broken core; 10cm avg length, reg frac @ 70°.	1				1	
10		51.82	53.34	GND core quite competent; broken along limonitic veinlets. Hematite staining noted in 1-3cm lengths. @ 52.17m: <1cm qtz vn alters GND (limonitic), as well at 53.1m. Aspy seen.	1	1	1		1	
10		53.34	54.86	GND. Pervasive limonite vning, random orient., competent core from 53.5-54.6m, rest is limonized & broken into 5cm blocks max.	1	1		1	1	
10		54.86	56.39	GND: small gouge section @ 55m, otherwise broken into ~5cm diam avg blocks w/ extensive 1mm vns of limonite. 2 qtz vns.	2	2		3	1	
10		56.39	57.91	Fewer mafics in GND where qtz is more smeared out (silicified zone). Aspy appears dissem @ 56.7m & 57.3m . These areas contain more competent core chunks up to 15cm long.	1		1	1		
10		57.91	58.80	Highly broken GND. Qtz vns (3) <2cm wide w/ no sulphides btwn 58.3-58.5m.	2	1		1	1	
10		58.80	59.44	Aspy appears in close proximity to qtz vn. 2 more qtz vns w/ dissem sulphides. Gouge @ 59.1m (adjacent to 2nd qtz vn).	2	1		2	1	
10		59.44	60.96	Competent section (low mafics) to 59.6m followed by limonite-pervasive gouge to fault breccia to 60.96m. Qtz found at 60.5m in centre of gouge material. No sulphides visible.	3	2		2	2	
10		60.96	62.48	Broken GND core. Qtz vns w/in most competent sections; no sulphides noted, no selvages.	2	1		2	2	
10		62.48	64.01	Extremely broken GND. Pc's 11cm long to gouge-sized particles. One thin (0.5cm) qtz vn at 62.5m w/ tiny alt'n ring.	3	2		3	2	
10		64.01	65.00	Gouge and remnant grains of GND to 64.5m. Rock is more competent @ 64.5m to 65.0m; blocks 10cm max.	4	3	2	2	2	
10		65.00	66.40	Pure qtz section to 65.3m. GND to 65.53m for 15cm, then GND to 66.4m. Dissem bt (1%) on frac faces. 5-sided rust print on one qtz sect (~4cm), no rxn rims visible.	1	1			1	
10		66.40	66.86	Angular gravel sized GND, some whole core.	1			1		5
10		66.86	68.02	Good recovery. 2cm qtz vn w/ dissem py & aspy. Near selvage, limonite stained frac perpendicular to vn.	1					5
10		68.02	68.58	Gouge contains remnant GND, qtz eyes, minor clay. Hydrothermal alt'n of GND.	2			1		4
10		68.58	69.98	Good recovery. White qtz vns at 65° & 35°. Minor dissem py & aspy, limonitic fracs.	1					5
10		69.98	70.46	Good recovery. <1cm qtz vns present. Minor dissem py & aspy.	1					5
10		70.46	71.24	White qtz vns at 40°, limonized fracs.	1					5
10		71.24	71.63	Broken GND, up to 10cm long. Limonized fracs, white qtz vn (1.5cm). Broken pc's qtz ~2cm, GND decomposed, hydrothermally alt'd.	2	1		2		3
10		71.63	72.92	Gravel-sized GND, rounded. Some clay present, qtz eyes, white qtz vn.	1					

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages												Oxidation				Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
																						B291033	42.65	44.20	0.101		VA05042605	1.55	
																						B291034	44.20	44.93	0.114		VA05042605	0.73	
1	1	1.0	1.0	80		0		0		2.0								2				B291035	44.93	45.72	0.069		VA05042605	0.79	
																						B291036	BLANK		<0.005		VA05042605		
	4	0.1	0.1															0				B291037	45.72	46.22	0.057		VA05042605	0.50	
2	1	1.0	2.0	10		0		0										0				B291038	46.22	47.92	0.073		VA05042605	1.70	
																						B291039	47.92	48.77	0.416		VA05042605	0.85	
																						B291040	48.77	49.50	0.058		VA05042605	0.73	
1	1	1.0	1.0	90		10		2		2.0			2.0					1				B291041	49.50	49.80	0.895		VA05042605	0.30	
1	1	1.0	1.0	90		10		2		2.0			2.0					1				B291042	49.50	49.80	0.222	DUP	VA05042605	0.30	
																						B291043	49.80	50.29	0.027		VA05042605	0.49	
3	1	1.0	3.0	45		1		2		0.0								0			s&cb	B291044	50.29	51.82	0.353		VA05042605	1.53	
2	1	0.5	1.0	80		2	s/cb	2		1.0			2.0									B291045	51.82	53.34	0.170		VA05042605	1.52	0.36
																						B291046	53.34	54.86	0.142		VA05042605	1.52	
2	1	0.5	1.0	50		2		2														B291047	54.86	56.39	0.191		VA05042605	1.53	
																						B291048	56.39	57.91	0.106		VA05042605	1.52	0.294
																						B291049	56.39	57.91	0.094	PD/CA	VA05042605	1.52	
																						B291050	STANDARD 3C		0.090	3C	VA05042605		
3	1	0.5	1.5	40		0		0		0.0												B291051	57.91	58.80	0.103		VA05042605	0.89	
3	1	1.0	3.0	70		2	cb/s	4					3.0									B291052	58.80	59.44	0.058		VA05042605	0.64	
1	1	1.0	1.0	60																		B291053	59.44	60.96	0.043		VA05042605	1.52	
3	1	0.5	1.5	50		0																B291054	60.96	62.48	5.580		VA05042605	1.52	
1	1	0.5	0.5	80		0																B291055	62.48	64.01	0.279		VA05042605	1.53	
																						B291056	BLANK		<0.005		VA05042605		
1	1	1.0	1.0	50		0																B291057	64.01	65.00	0.222		VA05042605	0.99	
2	1	10.0	15.0	60		0				0.0												B291058	65.00	66.40	0.025		VA05042605	1.40	
																						B291059	66.40	67.07	0.114		VA05042605	0.67	
2	1	2.0	3.0	55					1	2.0			1.0								lim	B291060	67.07	67.31	1.805		VA05042605	0.24	
																						B291061	67.31	68.02	0.196		VA05042605	0.71	
																						B291062	67.31	68.02	0.189	DUP	VA05042605	0.71	
																						B291063	68.02	68.58	0.698		VA05042605	0.56	
5	1	1.0	5.0	65	35				1	1.0											lim	B291064	68.58	69.98	0.089		VA05042605	1.40	
4	1	0.5	2.0	65	35				0	1.0			1.0									B291065	69.98	70.46	0.016		VA05042605	0.48	
3	1	1.5	4.0	40		0.5																B291066	70.46	71.24	0.148		VA05042605	0.78	
1	1	1.5	1.5																		lim	B291067	71.24	71.63	0.049		VA05042605	0.39	
1	1	1.0	1.0																			B291068	71.63	72.92	0.077		VA05042605	1.29	
1	1	1.0	1.0																			B291069	71.63	72.92	0.071	PD/CA	VA05042605	1.29	
																						B291070	STANDARD 3C		0.809	3C	VA05042605		

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		72.92	73.15	Qtz vns at top, in competent core, changes to gougy GND; hydrothermal alt'n related to qtz vning.	1			1		
10		73.15	74.02	Gravel-sized GND & qtz, rounded, limonized.	1					
10		74.02	74.49	Gouge, partially alt'd GND, clays w/ qtz eyes & gravel-sized GND, hydrothermal alt'n, limonitic.	2	1		2		
10		74.49	78.12	Broken core, limonized fracs. Qtz vn @ 45°, 8cm qtz lens at 77.72m, minor aspy in some vns.	1	1				
10		78.12	79.08	Good recovery. GND w/ qtz vns at 30°, minor aspy. Fracs show limonite. Py and strong sulphur smell present.						
10		79.08	80.37	GND w/ qtz vns at 30°, fracs are limonitic, dissem aspy btwn 80.19-80.37m, highly oxidized.	2					
10		80.37	80.70	2 massive sulphide vns ~3cm, aspy & scorodite & py present, GND highly alt'd, vuggy.	2					
10		80.70	82.30	Small qtz vns <1cm, limonized frac. Alt'd at 82.0-82.10m, gravel-sized GND w/ clay--hydrothermal.	2	1			1	
10		82.30	83.82	Good recovery. Limonized fracs, 7 qtz vns ~1cm thick, in conjugate sets, 2 series of vn emplacement. Gouge at 83.72-83.82m, qtz eyes present w/ remnant GND w/ hydrothermal alt'n.	1				1	
10		83.82	85.34	<1cm qtz vns in GND, limonized fracs alter rock from 83.22-83.42m. Qtz eyes & hydrothermally alt'd GND present. Preceded & followed by qtz vns at 45°.						
10		85.34	86.87	Good recovery. Limonized fracs, qtz vns <1cm, dissem aspy.	1	1		1		
10		86.87	87.35	Good recovery. Limonized fracs, 2 series of vn emplacement, 1st qtz at 45°, 2nd qtz & calc at 30°, minor aspy present in margins of both vns.	1					
10		87.35	87.93	Highly oxidized GND containing qtz & calc vns. Alt'd to clay w/ GND frags & qtz eyes from 87.65-87.75m. Hydrothermal continues after as oxidation w/ vns. Aspy present in qtz vn margin.	4	2				
10		87.93	88.39	Slightly oxidized GND hosting several small qtz vns. Vns are oxidized at margins. Aspy present in margins.	1					
10		88.39	89.38	Gravel-sized GND mixed w/ clay shows more intense alt'n after 88.8m; higher clay content & becoming crumbly. Qtz eyes present in the clay; possible fault or hydrothermal alt'n. Remnant GND in clay indicates hydrothermal more likely. Gravel size pc's of qtz, possible vns weathered.	2	1		2		
10		89.38	90.74	Slightly alt'd GND w/ limonized fracs grades to gravel sized GND btwn 89.92-90.06m. Qtz vns <1cm present, minor aspy in rim.	1	1		1		
10		90.74	90.99	Alt'd & oxidized GND. Brownish red in color, alt'd to sericite & clays. Qtz eyes present--hydrothermal.	3	1		2		
10		90.99	91.24	Highly oxidized & alt'd GND. Zone of intense clay alt'n; fault gouge at 91.09m, qtz vn <1cm.	3	2		3		
10		91.24	92.11	Mod ox'n & alt'n. Brownish red color. Mushy texture w/ qtz eyes & pebble sized GND; hydrothermal alt'n.	3	1		2		
10		92.11	92.96	Less ox'd & alt'd. Milky qtz vns <1cm. Small zones (1-2cm) of intense alt'n above & below vns. Qtz eyes present in zones; likely hydrothermal. Milky white qtz vns at 92.44m @ indeterminate angle w/ trace aspy at margin. Vn @ 92.70m: 0.5cm, grey, @ indeterminate angle due to alt'n, tr. aspy at margin.	2	1		1		
10		92.96	93.97	High alt'n btwn 92.96-93.14m. Mod alt'n (1) until 93.79-93.90m, which shows high alt'n to clays. Qtz vns at 70° to CA at 93.11m, 1cm diam. Vn @ 93.14m: 3.5cm @ 65° to CA, grey.	2	1		1		
10		93.97	94.49	Mod alt'n (2) until 94.03m where alt'n becomes higher (3). Qtz eyes present throughout clays & GND, likely hydrothermal alt'n. Minor sericite present.	2	1		2		
10		94.49	95.48	Slightly alt'd (1) but mod ox'n in GND. Highly alt'd (4) at 94.90-94.95m & at 95.32-95.38m to clay w/ qtz eyes & GND frags. Broken qtz vn @ 95.4m, grey.	3	1				
10		95.48	96.51	Good recovery. Mod ox'n in GND w/ limonitic fracs. Sericite in fracs & alt'n halos. Qtz vns @ 96.23m, ox'd vn w/ 3% ox'd py & 1% ox'd aspy in vn margin & halo.	2	1				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration, 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages												Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
4	1	1.5	2.5	65																		B291071	72.12	73.15	0.533		VA05042605	1.03	
																						B291072	73.15	74.02	0.235		VA05042605	0.87	
																						B291073	74.02	74.49	0.233		VA05042605	0.47	
2	1	1.5	2.5	45																		B291074	74.49	75.29	0.104		VA05042605	0.80	
5	1	2.0	7.0	45																		B291075	75.29	75.71	0.126		VA05042605	0.42	
																						B291076	BLANK		<0.005		VA05042605		
5	1	1.2	4.0	45																		B291077	75.71	76.76	0.154		VA05042605	1.05	
3	1	1.0	3.0	45																		B291078	76.76	78.12	0.356		VA05042605	1.36	
3	1	1.5	4.0	30		7	s	3	2	5.0					10						lim	B291079	78.12	79.08	9.990		VA05042605	0.96	
5	1	0.5	2.5	30																		B291080	79.08	79.40	0.692		VA05042605	0.32	
3	1	2.0	4.0	45																		B291081	79.40	79.90	0.682		VA05042605	0.50	
3	1	2.0	4.0	45					1				1.0								lim	B291082	79.40	79.90	0.443	DUP	VA05042605	0.50	
3	1	1.0	1.5	45														4				B291083	79.90	80.37	0.601		VA05042605	0.47	
2	6	3.0	5.0	40					2	5.0			25.0						4			B291084	80.37	80.70	2.530		VA05042605	0.33	
8	1	0.5	4.0	35																		B291085	80.70	82.30	0.348		VA05042605	1.60	
7	1	1.0	6.5	45	50								0.1					2				B291086	82.30	83.82	0.757		VA05042605	1.52	
6	1	1.0	4.5	45														2				B291087	83.82	85.34	0.230		VA05042605	1.52	
4	1	1.5	3.5	35		2	q	2	2				1.0									B291088	85.34	86.87	0.135		VA05042605	1.53	
4	1	1.5	3.5	35		2	q	2	2				1.0									B291089	85.34	86.87	0.187	PD/CA	VA05042605	1.53	
																						B291090	STANDARD 3C		0.090	3C	VA05042605		
4	1	1.0	2.0										1.0					1				B291091	86.87	87.35	0.468		VA05042605	0.48	
	3	0.2	2.0			2	q	3	3				1.0					1											
6	1	1.5	4.0	55		1	s	4	2				1.0					1				B291092	87.35	87.93	0.837		VA05042605	0.58	
	3	0.2	0.4																										
4	1	1.0	1.6	25									1.0									B291093	87.93	88.39	0.180		VA05042605	0.46	
																						B291094	88.39	89.38	0.190		VA05042605	0.99	
2	1	0.9	0.9										0.1									B291095	89.38	90.74	0.242		VA05042605	1.36	
																						B291096	BLANK		0.065		VA05042605		
																						B291097	90.74	90.99	9.530		VA05042605	0.25	
1	1	0.9	0.9																			B291098	90.99	91.24	0.657		VA05042605	0.25	
0																						B291099	91.24	92.11	0.261		VA05042605	0.87	
2	1	1.0	1.5										0.1									B291100	92.11	92.96	0.412		VA05042605	0.85	
2	1	3.5	4.5																			B291101	92.96	93.97	0.240		VA05042605	1.01	
																						B291102	92.96	93.97	0.125	DUP	VA05042605	1.01	
																						B291103	93.97	94.49	0.073		VA05042605	0.52	
1																						B291104	94.49	95.48	0.105		VA05042605	0.99	
1	1	0.2	0.2	30						3.0			1.0									B291105	95.48	96.51	0.162		VA05042605	1.03	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 7 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		96.51	97.54	Good recovery. Mod alt'd (2) & ox'd (2). Fracs show minor limonite. White qtz vns @ 96.84m, 1cm diam, contain 3% po in vns.	2	1				
				White qtz vn @ 97.14m, ox'd rim, 1cm, 35° to CA, 3% py in vns, ox'd py.						
10		97.54	98.10	Slightly alt'd GND. Less limonitic, minor in fracs. Vn @ 97.87m; 1cm milky white qtz @ 40° to CA contains cpy 1%, po 1%, aspy 3%, tr. magnetite. Microfault cuts vn.						
10		98.10	99.06	Good recovery. Minor ox'n from 98.92-99.06m. Fracs slightly limonitic. Grey qtz vn @ 98.85m @ 40°to CA. Grey qtz vn @ 98.9m; 0.5cm, ox'd margin.	1					
10		99.06	99.76	Mod alt'n (2-3) to sericite & clay. Qtz eyes & vns present, but are fractured & displaced. Hydrothermal or shear zone alt'n occurs at 45° to CA. White qtz vn @ 99.50-99.55m @ 60° to CA, tr py (ox) & aspy. Grey qtz vn @ 99.68m, 1cm, frac & displaced, 40° to CA.	1	2		2		
10		99.76	100.58	Start of good core. Weak limonite staining on fracs. Slightly alt'd, minor sericite in fracs. Vn @ 100.23m, 1cm at 40° to CA. no visible sulphides.	1	1		1		
10		100.58	102.11	Less ox'n than above. Vn @ 100.83m, 1cm at 40°, aspy in margin. Milky white qtz vns @ 101.15m, 101.19m, 101.33m, 1cm, tr aspy in margins @ 35°.	1			1		
10		102.11	103.63	Slightly altered GND - minor limonite on fracs. Vein @ 103.44: white qtz	1					
10		103.63	105.16	Slightly oxidized GND. V. little limonite in fracs. Veins run near parallel to CA w/ ox'd margins; py & aspy in margins						
10		105.16	106.68	Relatively unaltered GND. Limonite in fracs. Veins run parallel to CA. Aspy & py in margins. Py slightly oxidized						
10		106.68	108.20	Unaltered GND w/ minor limonite in fracs. Vein at 106.68-106.86m, 0.1cm, ox'd, white qtz at 45° to CA . Vn @ 106.90m: 1cm, grey, @40° to CA, 5% ox'd po, 1% ox'd py. Vein at 107.95m. 0.1cm white qtz with carbonate, at 70°, trace aspy.	1					
10		108.20	109.73	Core is fractured. Lim on few surfaces, qtz & carb veinlets					1	
10		109.73	110.34	Unaltered GND. Minor limonite on fractures. Vn @ 109.77: 0.5cm, at 50°, trace aspy, milky white qtz, offset by micro-fault. Veins at 109.97m and 110.19m, milky white qtz, at 40° to CA, minor po and trace cpy in veins.						
10		110.34	111.25	Unaltered GND. Minor limonite on fractures.						
10		111.25	112.05	Good recovery. Minor ox'n. Stain in fracs. GND is lightly bleached. Dissem po (5%) & aspy (tr.) & py (1%) through entire length.						
10		112.05	113.66	~30% ser alt'n around narrow veins. 13 veins noted. Angles are complimentary (45° & 145°)	1	3	1		1	
10		113.66	114.60	Section is entirely altered w/ sericite + ox'n w/ lim covering fracture planes	3	3	2	1		
10		114.30	115.09	GND same as above unit, but veins/fractures more randomly oriented (20-90°)	3	3	2	1		
10		115.09	116.05	1mm carb/ser. Veins fractured at reg angle: 125°/65°; these tiny veins overprint larger qtz veins w/ sulphides at 145°/35°	1	2	1		1	
10		116.05	116.80	4 qtz. vns. Have clear centres(1cm, max) w/ margins of milky qtz (1cm thick). Py & aspy are in granular clumps on margins and w/l clear qtz centres. Ser/qtz/carb veins: <1mm thick, ox'd. More frequent w/ fractures	1	1	2		1	
10		116.80	117.80	Zone of high alteration but rock is still coherent, except at 117.25 where clay alteration is ~5cm thick. Med. grade, low-angle fracturing has slickensides shown in sericite, perpendicular to breaking plane's long axis. Sulphides appear at margins of fault breccia section (117.05 - 117.13m). Massive sulphides w/ aspy @ exterior edges. py clumped into masses >8cm long and 1cm wide. At 117.5m, v. high chlorite alt'n; only indistinct qtz. grains left. Some are in lines, denoting overprinted veins between 117.45 to 117.80m. Trace po located w/in these lines.	1	3	3	1	1	

DRILL LOG LEGEND P2

Date: May 23 to 27th, 2005

PAGE 8 of 22

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS											% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages												Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
2	1	1.0	2.0	35						3.0	3											B291106	96.51	97.54	0.197		VA05042605	1.03	
2	1	1.0	1.5	40							1	1.0	3.0									B291107	97.54	98.10	4.000		VA05042605	0.56	
2	1	0.5	1.0	40																		B291108	98.10	99.06	0.064		VA05042605	0.96	
2	1	0.5	1.0	40																		B291109	98.10	99.06	0.068	PD/CA	VA05042605	0.96	
																						B291110	STANDARD 2B		3.180	2B	VA05042605		
2	1	1.0	2.0	40						0.1			0.1									B291111	99.06	99.76	0.470		VA05042605	0.70	
1	1	1.0	1.0	40																		B291112	99.76	100.58	0.767		VA05042605	0.82	
4	1	1.0	4.0	40	35								0.1									B291113	100.58	102.11	0.831		VA05042605	1.53	
1	1	1.0	1.0	40																		B291114	102.11	103.63	0.035		VA05045435	1.52	
1	1	1.0	1.0	85					2				0.1									B291115	103.63	105.16	0.131		VA05045435	1.53	
																						B291116	BLANK		<0.005		VA05045435		
1	1	0.1	0.1	85		2	q	3	1	1.0			0.1									B291117	105.16	106.68	0.022		VA05045435	1.52	
3	2	1.0	1.1			2	q	2	2	1.0	5											B291118	106.68	108.20	0.036		VA05045435	1.52	
	3	0.1	0.1										0.1														VA05045435		
2	1	1.5	2.5	35	40				1	1.0			3.0					3				B291119	108.20	109.73	0.159		VA05045435	1.53	
3	1	1.0	2.7	50		1	q	2	1		1	0.1	0.1									B291120	109.73	110.34	0.035		VA05045435	0.61	
3	1	1.0	3.0	45							10											B291121	110.34	111.25	0.466		VA05045435	0.91	
3	1	1.0	3.0	45							10											B291122	110.34	111.25	0.477	DUP	VA05045435	0.91	
1	1	1.0	1.0	50							0.1											B291123	111.25	112.05	0.313		VA05045435	0.80	
10	4	0.2	2.0	45	145	6	s/cb	2	3	2.0												B291124	112.05	113.66	0.090		VA05045435	1.61	
3	3	1.0	3.0	45	135	1	q/chl	1	0	4.0			5.0																
2	3	1.5	2.0	30		2	chl/s/cb	3	3	1.0												B291125	113.66	114.30	0.470		VA05045435	0.64	
8	3	1.0	4.5			2	chl/s/cb	3	3	1.0												B291126	114.30	115.09	0.041		VA05045435	0.79	
3	1	3.0	8.0	145	35	4	chl/s/cb	2	2													B291127	115.09	116.05	0.192		VA05045435	0.96	
2	3	0.2	0.5	65	125					2.0			2.0																
3	1	4.0	7.0	25	45					0.1			2.0									B291128	116.05	116.80	0.237		VA05045435	0.75	
3	1	4.0	7.0	25	45					0.1			2.0									B291129	116.05	116.80	0.294	PD/CA	VA05045435	0.75	
																						B291130	STANDARD 4D		0.479	4D	VA05045435		
3	1	3.0	5.0	40		10	chl/s	3	0.5	8.0	0.1	0.1	2.0									B291131	116.80	117.80	0.256		VA05045435	1.00	
1	6	1.0	1.0	40	50																								

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.80	118.24	Relatively unaltered. Pervasive lens of sericite appears associated w/ qtz lens. Small, partially ox'd carb veins overprinting ser & qtz.	1	2	1	1	1	
10		118.24	118.97	Altered around 3 qtz veins.	0	2	1	1	1	
10		118.97	119.40	Angle at which altered zone turns to unaltered GND is 45°. Sample is unaltered GND. Lenses of po < 4cm long & 0.3cm wide seen adjacent to qtz vein at 119.30m						
10		119.40	119.59	2cm wide milky qtz vn has po & py concentrated in 0.5cm wide section in centre						
10		119.59	121.10	2cm² section of po (uneven cluster). @119.90m, a section of randomly-oriented veinlets of calcite plus one 0.5cm vein of massive sulphides (po, py & cpy) rimmed w/ calcite, to 30°. Qtz vein at 120.11m to 140° not much alt'n assoc. Rest of section relatively unalt'd GND. Qtz veins: @120.16m, 120.47m, 120.76m, 120.86m, 121.02m & 121.20m. All @45-50° to CA. These veins have inner sections of clear qtz, a few mm thick, and outer sections of milky qtz. Po and py seen inside clear qtz.						
10		121.10	122.20	Six qtz veins noted, to 121.43m, after which, there is a zone of highly alt'd (chl+ser) GND. Bleached zone at 121.5m, at 55° to CA, with 0.5cm qtz vein in centre. Qtz vein also at 55°, at 121.6m begins chl alt'n zone to 121.85m. 3cm sericite zone btwn 2 qtz veins 1cm thick; alt'd zone to 122.2m.		1	1		1	
10		122.20	123.50	Silicified sections 3cm wide w/ 3cm alteration halos at 122.27m, 122.4m, 122.63m & 123.2m. Orientation is always 45°. 1-2% py & po w/in bleached sections. 3 qtz veins @ 122.5m, 122.9m and 123.4m @50° to CA.						
10		123.50	125.00	GND w/ altered/bleached sections: 123.65-123.90m (gouge, last 4cm); 124.10-124.14m; 124.50-124.53m; 124.84-124.68m; 124.78-124.83m. Two of these sections have small qtz veins at centre.	0	3	2	2	1	
10		125.00	125.90	GND w/ altered sections: 125.65-125.66m; 125.79-125.80m; 126.40-126.60m.	0	3	1	1	1	
10		125.90	127.39	Sericitized & chloritized GND assoc. w/ 10 1-2cm qtz vns w/ sulphides. Vn locations: 125.9m (70°), 126.17m (60°), 126.23m (40°), 126.4m (70°), 126.44m (70°), 126.64m (70°), 126.74m (50°), 126.90m (40°), 127.26m (50°), & 127.35m (40°). Aspy concentrated @ margins of veins, py w/in vein and at margins	0	3	3	0	1	
10		127.39	128.66	Continued zone of alteration except from 127.39 → 127.5 where veins are <1mm and selvages <2cm Larger qtz veins w/ sulphides @ 127.88, 128.16, 128.21, 128.44 & 128.63m; sulphides situated similar to above.	0	3	3	1	1	
10		128.66	129.64	Sericite & chlorite GND. Qtz veins: @128.89m (60°); @129.42m (60°), trace aspy; @129.95m (90°), trace po; @129.45m (40°).						
10		129.64	131.10	Qtz veins contain trace po & as, lots of py, located: @129.89m (70°), @130.50m (70°), @130.68m (65°). Massive sulphide lens at 129.8-129.85m, 3cm wide. Tr po, py, aspy. Section is mostly s/chl alt'd w/ <10cm wide unalt'd sections.		3	3	1	1	
10		131.10	132.04	Qtz vein at 131.15m at low angle and contains no sulphides. Others, at high angle, contain po. Veinlet network of carbs surrounded by selvages of silicified GND (bleached)					1	
10		132.04	134.23	Unaltered GND w/ carb veinlets randomly oriented w/in. Bleached sections @132.34m (70°), 4cm wide; @132.84m (45°), 12cm wide; and @132.92m (45°), 2cm wide. These may be silicified veins; aspy and py in moderate amounts. Late calcite veinlets offset qtz vein offshoots to 20°. Qtz veins: @133.80m, to 35°, 3.5cm thick; @134.0m, to 35°, 0.3cm thick; and @134.08m, 35°, 1cm thick.		2	1			
10		134.23	134.70	Unaltered GND. Silicified qtz vein at 134.35m, to 45° w/ no sulphides. Vn at 134.52m, 60°, w/ assc po. Qtz/carb vein at 134.62m, at 45° to CA, w/ high percentage of po.		1				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration, 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	45		0.5	s/chl	2	0	2.0	2		0.1									B291132	117.80	118.24	0.037		VA05045435	0.44	
3	1	1.0	3.0			4	chl/sericite	2														B291133	118.24	118.97	0.082		VA05045435	0.73	
1	1	1.0	1.0	45		0.5	chl/q	1			2											B291134	118.97	119.40	0.062		VA05045435	0.43	
1	1	3.0	3.0	80		4	q/chl			1.0	5											B291135	119.40	119.59	0.125		VA05045435	0.19	
																						B291136	BLANK		<0.005		VA05045435		
1	1	1.0	1.0	140		1.5				1.0												B291137	119.59	121.10	0.926		VA05045435	1.51	
11	1	1.5	7.5	45		1	s/chl	1		0.1			0.1									B291138	121.10	122.20	0.716		VA05045435	1.10	
3	1	1.5	3.0	50		1	s/chl	1		2.0												B291139	122.20	123.50	0.413		VA05045435	1.30	
3	1	3.0	9.0	45		4				2.0	2																		
2	1	0.5	1.0	45		1	s/chl	2														B291140	123.50	125.00	0.972		VA05045435	1.50	
1	1	0.5	0.5	50		1	s/chl	1					3.0									B291141	125.00	125.90	0.049		VA05045435	0.90	
1	1	0.5	0.5	50		1	s/chl	1					3.0									B291142	125.00	125.90	0.062	DUP	VA05045435	0.90	
10	1	2.0	9.0	70	45	10	s/chl	4		4.0			3.0									B291143	125.90	127.39	0.165		VA05045435	1.49	
5	1	1.5	4.0	55	25	10	s/chl	4		4.0			2.0									B291144	127.39	128.66	0.492		VA05045435	1.27	
3	1	1.0	3.0	60	40	10	s/chl	5					0.1									B291145	128.66	129.64	1.195		VA05045435	0.98	
1	1	1.0	1.0	90		5	s/chl	5			0.1																		
3	1	2.0	4.0	70	65	0.5	s/chl	4		10.0	0.1		0.1									B291146	129.64	131.10	3.280		VA05045435	1.46	
1	6	3.0	3.0			10	s/chl	5		0.1	0.1		0.1																
1	1	1.0	1.0	55		0.5	s	1			10											B291147	131.10	132.40	0.478		VA05045435	1.30	
1	1	1.0	1.0	15		0.5	s	1																					
2	4	0.2	0.4	25	35	1	cb/q	2	1													B291148	132.04	133.22	0.628		VA05045435	1.18	
						12	cb/q	3		3.0			2.0																
2	4	0.2	0.4	25	35	1	cb/q	2	1													B291149	132.04	133.22	0.621	PD/CA	VA05045435	1.18	
						12	cb/q	3		3.0			2.0																
																						B291150	STANDARD 4D		0.475	4D	VA05045435		
3	1	3.5	7.0	35		10	s/chl/q	4	1	2.0	1		1.0									B291151	133.22	134.23	0.425		VA05045435	1.01	
1	1	2.0	3.0	50	20		s/chl				0.1																		
1	1	1.0	1.0	45		1	s/chl	1			0.0											B291152	134.23	134.70	0.288		VA05045435	0.47	
1	1	1.0	1.0	45		1	q	1			20.0																		
1	1	0.6	0.6	60		1	q	1			5.0																		

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		134.70	135.64	At 134.70m, turns to alt'd at an angle of 40°. Qtz veins: @135.01m (50°); @135.22m (25°); @135.27 (50°) - intersects with previous, same generation; @135.54 (45°). At 135.34m, alt'd turns to unalt'd at a 40° angle.	1	4	3	2	2	
10		135.64	137.16	Unaltered GND except from 136.18→136.26m where chl zone surrounds 0.5cm qtz vein at 50°, and from 136.59 to 137.12m around 1cm qtz vein at 70° to CA. Also in this interval at similar angles are veinlets of 'pure' sulphides surrounded by bleached sections, 2cm wide, within alt zone			1			
10		137.16	137.59	GND has multiple 1-2cm thick qtz veins @ an average angle of 40-60° to C.A., ~1-2% dissem py and aspy present within milky white qtz veins. Core is devoid of limonite staining. GND is still of consistent mineralogical nature, however, episodes of bleaching/leaching of minerals out have reduced sections to extremely sericitic/bleached and occasionally silicified veins @ 137.20m (@ 50°), 137.34 (@40°), w/ dissem py, po, aspy. Sericite on margins						
10		137.59	140.03	GND is extremely bleached. Feldspars have completely reduced with rare to minor (<2%) mafics within GND Clear qtz vns @: 137.69, 137.76, 137.87, 137.95, 138.05, 138.07. 0.25-0.50cm, @50° to CA, w/ tr. euhedral po. and trace aspy. Milky to clear qtz veins after 138.83m contain po.						
10		140.05	140.45	Unaltered GND. Minor sericite on margin of bleached GND		1				
				@ 140.35: milky qtz w/ dissem po						
10		140.45	140.80	Bleached GND w/ trace mafics. Contact w/ unaltered GND @ 45°. Tr. dissem. aspy & po appear to be vein-like in orientation, @~50° to CA, however no clear vn materials present						
10		140.80	142.49	Unaltered GND predominant w/ veining (qtz) and sericite sections as well as on fractures (from 141.85 - 142.49m pervasive). 0.5 to 1.0cm milky qtz vns w/ clear qtz centres contain trace po and aspy. Ser minor, present on margins. Vns ave at 50° to CA.						
10		142.49	143.33	Extremely bleached, sericite-rich, grey white GND. Tr. indiscernible sulphides. Core is easily scratched w/ a nail		1				
10		143.33	143.63	Both qtz veins contact CA at 35°. Disseminated aspy 2-4%. disseminated py 1-2%						
10		143.63	145.30	Extremely bleached, sericite rich, grey white GND. Tr. indiscernible sulphs. Core is easily scratched w/ a nail. At 144.10m, 0.5cm qtz vein w/ 10% disseminated po.						
10		145.30	145.56	Extremely bleached GND w/ abundant sericite adjacent to 9cm thick massive sulphide vn; 90% aspy, 10% py.						
10		145.56	147.60	Slightly green sericitic GND w/ extensive bleaching. Soft core, yet coherent. Minor 0.5-1cm qtz veining		1				
10		147.60	147.83	Fault gouge. Greenish grey clay with sulphide-looking oxidized material. No visible fresh sulphides	2					
10		147.83	148.33	Bleached and sericite rich, broken GND. Core has green sericite hue						
10		148.33	150.53	GND w/ minor sericitic partings marked by soft, green hued core. Minor carbonate veinlets. Veins: @149.37m, 149.48m, 149.52m & 149.59m, 0.25-0.5cm qtz veins with trace euhedral-subhedral po. Vns @ 40-50° to CA. At 150.16m, 150.32m, 150.38m and 150.43m, 0.5-1cm qtz veins @ 50° to CA, trace aspy.						
10		150.53	150.88	Bleached GND w/ 3 1cm qtz vns @50° to CA w/ trace disseminated aspy & po.						
10		150.88	151.20	Fault gouge, uniform light grey clay w/ minor visible qtz eyes. Appears to have ox'd sulphides mixed in, but inconclusive	1	2		5		
10		151.20	152.66	Broken GND w/ sericite-coated fracs and minor sericite partings -- Semi-decomposed GND. One 2cm qtz vein w/ no visible sulphides		3		1		
10		152.66	153.35	Highly bleached, altered GND. Abundant sericite both pervasive and on fracs. Minor sericite/clay partings		3		1		

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Pnm Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	3.0	5.5	45		10	s/chl	4														B291153	134.70	135.64	0.655		VA05045435	0.94	
3	1	1.5	3.0	50	70	12	s/chl/q	3		10.0												B291154	135.64	137.16	1.525		VA05045435	1.52	
10	1	2.5	6.0								2.0		0.1									B291155	137.16	137.69	0.359		VA05045435	0.53	
																						B291156	BLANK		<0.005		VA05045435		
6	1	0.5	3.0	50																		B291157	137.69	138.68	0.860		VA05045435	0.99	
3	1	2.0	3.3	60							2.0											B291158	138.68	140.21	0.174		VA05045435	1.53	
6	1	1.5	3.0					1			0.1											B291159	140.21	141.73	0.141		VA05045435	1.52	
6	1	1.0	4.0					1			0.1		0.1									B291160	141.73	142.49	0.206		VA05045435	0.76	
2	1	0.5	1.5					4														B291161	142.49	143.33	0.211		VA05045435	0.84	
2	1	0.5	1.5					4														B291162	142.49	143.33	0.145	DUP	VA05045435	0.84	
1		28.0								2.0			4.0	0.1								B291163	143.33	143.63	18.750		VA05045435	0.30	
2		0.5	1.0					4			0.1											B291164	143.63	144.78	0.884		VA05045435	1.15	
1		0.5	0.5					3														B291165	144.78	145.30	0.194		VA05045435	0.52	
1	6	9.0	9.0					0		10.0			90.0						0.1			B291166	145.30	145.56	1.490		VA05045435	0.26	
2	1	1.0	1.5	60	25								0.1									B291167	145.56	146.30	1.240		VA05045435	0.74	
																						B291168	146.30	147.41	0.261		VA05045435	1.11	
																						B291169	146.30	147.41	0.265	PD/CA	VA05045435	1.11	
																						B291170	STANDARD 4D		0.462	4D	VA05045435		
																						B291171	147.41	147.83	0.212		VA05045435	0.42	
																						B291172	147.83	148.83	0.091		VA05045435	1.00	
4	1	0.5	2.0	40	50						0.1											B291173	148.33	149.35	0.096		VA05045435	1.02	
4	1	1.0	3.0	50									0.1									B291174	149.35	150.53	1.550		VA05045435	1.18	
3	1	1.0	3.0	50							0.1		0.1									B291175	150.53	151.10	5.130		VA05045435	0.57	
																						B291176	BLANK		0.005		VA05045435		
1	1	2.0	2.0	50																		B291177	151.10	152.40	0.404		VA05045435	1.30	
6	1	1.0		35	50					1.0			1.0									B291178	152.40	153.92	1.840		VA05045435	1.52	

DRILL LOG LEGEND -- P1	DATE: May 23 - 27th, 2005 PAGE 13 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		153.35	157.25	Mostly unaltered GND w/ qtz vns containing trace to 1% dissem sulphides, minor sericite on vn margins. At 153.34m, 153.40m, 153.60m, 153.63 and 153.71m, qtz veins 0.25-1.0cm thick, @ 35°-50° to CA contain tr-1% disseminated py, aspy. At 154.07m, a 1.5cm qtz/sulphide vein at 50° to CA contains 5% aspy and 1-2% py. At 154.12, 154.23, 154.31, 154.41, 154.43, 154.53, 153.62, 154.65, 154.70, 154.76, 154.85, 154.97 and 155.00m, 0.25-1cm thick qtz veins with trace-1% disseminated po and trace to no arsenopyrite. Average range of vn angles is 25-50° to CA. @155.42, 0.5cm thick qtz vn @50° to CA, w/ tr diss po. One 0.25cm carbonate (dolomite) vein at 156.06m, at 60° to CA contains trace py and ~1% aspy.		2		1		
10		157.25	158.01	GND becomes highly sericitized: soft, has green hue. Multiple qtz veinlets: @157.07, 157.27, 157.38, 157.42, 157.50 and 157.56m, 40-50° to CA, up to 0.5cm, max; most w/ tr. po and tr aspy.						
10		158.01	158.22	Qtz/sulphide veins and veinlet stringers within qtz veins and x-cutting throughout GND. Within the sulphide veins the py seems to always be central w/ the aspy on the margins. Dissem sulphides throughout GND section. At 158.08m, two 1-2cm thick sulphide veins at 50° to CA, contain 60% py and 40% aspy.						
10		158.22	158.50	Broken sericite abundant pervasive. Hydro-alt'd GND appears to be a fault zone. Plenty of bleached clay and qtz eyes.		3	1	3		
10		158.50	160.02	Altered, bleached GND with pervasive sericite alteration, soft core. Minor disseminations/ veinlets/ blebs of sulphides. Commonly, py~1%, as~tr.-1%						
10		160.02	160.15	Semi-massive to massive py ~99% and aspy~1%, @55-60° to CA. Some qtz veining immediately adjacent on margins.						
10		160.15	162.47	Extremely altered/sericitic. Decomposed yet coherent GND. Core has yellow/green bleached hue. Minor qtz veinlets @ 50-60° w/ tr. dissem aspy/py in half of them.		4	1	1		
10		162.47	163.50	Unaltered GND w/ veinlets of disseminated aspy (~50% of qtz vein) @40-50° to CA.						
10		163.50	165.15	Mod sericite alt'd GND. Core is mod. broken w/ occasional veinlets of qtz/dissem. sulphs. Core is v. soft and is bleached. Typical veinlets @ 50° w/ disseminated blebs of subhedral po.		4	1	1	1	
10		165.15	167.42	From 165.15-165.84m, highly altered/bleached clay. GND core is retained but pure white/grey clay veins		5		5		
10		167.42	168.13	Unaltered GND w/ sericite on fractures. Couple of qtz veins @50° to CA, w/ tr-1% po within centre of vein		1		1		
10		168.13	168.58	45cm wide milky qtz vein. Tr sulphs (indistinguishable). Contact angle is 30° to CA						
10		168.58	171.33	Moderately bleached/altered GND w/ sericite abundant on fracs. Minor sulphide/qtz veinlets. Core is moderately coherent. 3 notable veins @: 168.77, 170.10, 171.06m. Qtz veins w/ tr. dissem po and aspy, 2.5, 1, 0.5cm thick respectively. Two at 55°, last one at 80° to CA.						
10		171.33	172.21	GND is extremely bleached, but peppered w/ disseminated sulphs. Predominantly aspy (5-8%) w/ tr. py						
10		172.21	173.85	GND is moderately altered in partings and bleached white/grey. Core is mod-very broken, can't obtain angles from vein frags. Appears to be a few >1cm thick veins in section. Sericite on fracs and occasionally pervasive		2				
10		173.85	180.00	An extremely altered section of GND. Core appears as qtz/sericite and moderate chlorite. Core is silicified and alt mafics are essentially altered. Some qtz veins can be seen w/ dissem. po (tr.)		3	3			
				@175.95: a clay faulted unit w/ a decomposed vn of aspy adjacent, poor core recovery. However the clay is of the graphite texture/colour w/ aspy observable. The aspy vn that remains is 1cm thick at 70° to CA. chl + ser abundant at 185.0 onward.		4	2	5		
				From 178.31 to 178.51m, qtz boudins and stringers of aspy and py. py~10%, aspy 20%. remainder of interval is of sericite and minor chl. Interpreted contact angles are 75-80° to CA.		3	1			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
16	1	1.0	7.0					2		2.0			4.0									B291179	153.92	155.31	2.850		VA05045435	1.39	
2	1	0.5	0.75	50	60						0.1		1.0									B291180	155.31	156.97	0.304		VA05045435	1.66	
14		1.0	3.5					2			0.1		0.1									B291181	156.97	158.01	0.865		VA05045435	1.04	
14		1.0	3.5					2			0.1		0.1									B291182	156.97	158.01	1.545	DUP	VA05045435	1.04	
3		0.5	1.0					3		2.0			2.0									B291183	158.01	158.50	0.622		VA05045435	0.49	
3		0.5	2.0					3		0.1	0.1		0.1									B291184	158.50	160.02	0.264		VA05045435	1.52	
3		1.5	16.0					1		99.0			1.0									B291185	160.02	160.15	8.120		VA05045435	0.13	
2		0.5	1.0					3		0.1			0.1									B291186	160.15	161.54	0.724		VA05045435	1.39	
4		1.0	2.0					3		0.1			0.1									B291187	161.54	162.47	0.236		VA05045435	0.93	
12		0.2	1.0							0.1			1.0									B291188	162.47	163.50	0.463		VA05045435	1.03	
12		0.2	1.0							0.1			1.0									B291189	162.47	163.50	0.311	PD/CA	VA05045435	1.03	
																						B291190	STANDARD 3C		0.092	3C	VA05045435		
9		0.25	1.0	50				1		0.1			0.1									B291191	163.50	164.54	1.395		VA05045435	1.04	
4		0.5	3.0	50				3		0.1			0.1									B291192	164.54	166.12	1.175		VA05045435	1.58	
5		0.75	3.0	50				1					0.1									B291193	166.12	167.64	0.368		VA05045435	1.52	
2		0.5	1.0	45				2			0.1		0.1									B291194	167.64	168.13	0.107		VA05045435	0.49	
								3														B291195	168.13	168.58	2.320		VA05045435	0.45	
																						B291196	BLANK		<0.005		VA05045435		
4		2.0	5.0	50				1		0.1	0.1		0.1									B291197	168.58	169.16	0.817		VA05045435	0.58	
3		0.25	3.0	50				2		0.1	0.1		0.1									B291198	169.16	170.69	0.741		VA05045435	1.53	
2		0.5	1.0	50				2			0.1		0.1									B291199	170.69	172.21	1.950		VA05045435	1.52	
																						B291200	172.21	173.74	0.554		VA05045435	1.53	
																						B291201	173.74	175.26	0.154		VA05045435	1.52	
																						B291202	173.74	175.26	0.228	DUP	VA05045435	1.52	
10	1	0.3	4.0	50				2														B291203	175.26	176.78	1.065		VA05045435	1.52	
																						B291204	176.78	178.31	0.348		VA05045435	1.53	
																						B291205	178.31	178.51	0.487		VA05045435	0.20	
																						B291206	178.51	180.00	0.586		VA05045435	1.49	

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.00	181.57	V. minor altered GND. Sheeted qtz veins/veinlets @ ave 40° to CA w/ occasional dissem. sulphides (inconclusive type, tr po)		1	1	1		
10		181.57	182.88	Mod. altered GND. Core appears as bleached greenish hue colour, chlorite is clearly present. Core is soft. Sericite is pervasive and abundant		4	3			
10		182.88	188.98	GND broken although core recovery is 90%. Minor sericite on fracs. Predominant dissem sulph. w/in the vns is po w/ lesser amounts of aspy. Veins are sheeted and relatively constant in thickness ranging from 0.5-1cm. Qtz veins milky to clear.		1	1	1	1	
10		188.98	189.23	GND as above						
10		189.23	191.09	Fault gouge. Light, bleached remnant of former GND due to visible brecciated pieces. Core is broken adjacent to fault and then retains its former competency 20cm distally. no visible sulphides. only qtz eyes and breccia. fault angle: 40-45°						
				At 190.56m, a 5cm wide qtz vein @ 50-55° to CA w/ minor biotite inclusive, very siliceous w/ tr. po.						
				Sulphide vein @ 191.00m, 0.5cm thick, w/ 96% po and 4% aspy, @ 60° to CA.						
10		191.09	191.29	Fault zone, focussed @ 191.19m. Core increases toward fault marked by aspy and grey, ox'd aspy. Also present are slickenside surfaces in sericitized/chloritized GND. Interval appears green/cream-coloured w/ mafics absent		3	3			
10		191.35	194.24	Same as above unit, however centrally the core is competent but has two 2cm qtz veins w/ dissem sulphides, at 50° to CA						
10		195.01	195.58	Silicified, bleached/altered GND. Core has white/green hue, devoid of mafics. Chlorite and sericite dominant with qtz veinlets at 50-60° to CA, w/ rare diss sulphides (po).		2	1			
10		195.58	195.64	Fault gouge w/ bleached GND. Breccia. Fault @ 50-55° to CA.		3	1	4		2
10		197.48	197.81	GND is alt'd to soft, sericite-rich and chlorite. Core is bleached and has a green hue. @197.59m, a graphite grey slickenside surface indicating faulting thus hydro fluids interpreted to alter GND to observed state, mafics almost non-existent						
				At 198.79m, a 2.5cm qtz vein @50-55° w/ tr. po. At 199.03m, 4.5cm qtz vein @40-45° w/ dissem. tr. po. At 199.91, 201.52 & 201.73m, qtz veins 2cm wide, @50° to CA with trace po.						
10		203.10	207.26	GND has abundant sheeted veins @45-50° to CA, typically 0.5-1.0cm wide, carrying ~1% po as disseminations. GND is mostly unaltered w/ v. minor sericite locals. veins spaced 5-10cm apart						
10		207.26	208.56	GND; Good recovery. Veins at 207.56m, milky white qtz, @60°, 1% cpy in vein, 30% ox'd, 0.2% aspy in margin. At 207.66m, a 3cm milky white qtz vein @70° to CA, 2% cpy, 50% ox'd. Veins at 207.74, 207.77 & 207.82m, 0.5cm, milky white @60° to CA - 1-3% cpy in vein, 30-50% ox'd, 0.2% aspy in margins. Veins at 208.48, 208.55, 208.56 & 208.61m, 0.2cm milky white qtz sheeted veins - 1% cpy in veins, trace aspy in margins.						
10		208.56	208.79	GND is bleached, grey-green colour. Sheeted vein set: at 208.60, 208.67 & 208.71m, 0.2cm, light grey qtz @ 35° to CA. Vein at 208.60m has 4cm selvage containing 3-5% po, 0.2% aspy.			2			
10		208.79	208.92	GND is brecciated, qtz frags present. 3% py (50% ox'd) present in broken qtz piece. Possible hydrothermal alt'n.						
10		208.92	209.69	GND altered to green-chlorite. Vein @ 209.09m, 2cm grey qtz @ 30° to CA, 1%py in vein, 10% ox'd. Vein @ 209.71m, milky white qtz @ 30° to CA, 15% py, 10% ox'd. Vein @ 209.42m, 1cm grey qtz @ 60° to CA, crosscut by 2cm qtz vein @ 40° to CA; 5% py in margin of crosscutting vein.			4			
10		209.69	210.39	GND altered to sugary texture. Whitish green colour. Qtz eyes present. Veins @ 209.86 @ 45° to CA, 2cm qtz vein, highly fractured, milky to grey in colour.		4				
10		210.39	211.13	mod. alt. GND, chloritic. Veins @ 210.49 & 210.80m. Milky white qtz @ 45° to CA; 0.2% aspy in vein. Core becomes highly fractured at end.			3			
10		211.13	212.14	Broken GND. Minor clay on fractures. Vein @ 211.33m, 1cm milky white qtz @ 45°						
10		212.14	212.90	GND altered to green-grey colour - chloritized. Disseminated aspy (70% ox'd) present throughout interval		1	4	1		

DRILL LOG LEGEND P2

Date: May 23 to 27th, 2005

PAGE 16 of 22

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages											Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
																						B291207	180.00	181.36	2.430		VA05045435	1.36	
																						B291208	181.36	182.88	1.000		VA05045435	1.52	
																						B291209	181.36	182.88	0.917	PD/CA	VA05045435	1.52	
																						B291210	STANDARD 2B		3.280	2B	VA05045435		
																						B291211	182.88	184.40	0.846		VA05045435	1.52	
4	1	0.5	1.0	50																		B291212	184.40	185.93	1.270		VA05045435	1.53	
5	1	0.5	3.0	45						0.1	5		0.1									B291213	185.93	187.45	0.707		VA05045435	1.52	
10	1	0.5	5.0	45	50					0.1	5		1.0									B291214	187.45	188.98	0.554		VA05045435	1.53	
8	1	0.5	3.0	45	50						2		0.1									B291215	188.98	190.50	0.110		VA05045435	1.52	
																						B291216	BLANK		0.005		VA05045435		
7	1	2.0	4.0	45	50					1.0	2		1.0									B291217	190.50	192.02	0.853		VA05045435	1.52	
1	6	0.5	0.5	60							96		4.0																
9	1	1.0	6.0	45	50					0.1	2		0.1									B291218	192.02	193.55	0.201		VA05045435	1.53	
8	1	1.0	5.0	40	50						2		1.0									B291219	193.55	195.07	0.910		VA05045435	1.52	
7	1	2.0	4.0	55	60								0.1									B291220	195.07	196.60	0.711		VA05045435	1.53	
4	1	1.0	2.5	50							1		0.1									B291221	196.06	197.48	0.781		VA05045435	1.42	
4	1	1.0	2.5	50							1		0.1									B291222	196.06	197.48	3.250	DUP	VA05045435	1.42	
3	1	0.5	1	50							1		1.0									B291223	197.48	198.12	1.625		VA05045435	0.64	
9	1	4	7	45	50					0.1	2		1.0									B291224	198.12	199.64	1.745		VA05045435	1.52	
8	1	2.5	3.5	45	50						2		1.0									B291225	199.64	201.17	1.030		VA05045435	1.53	
6	1	2	5	45	50						1		0.1									B291226	201.17	202.69	0.899		VA05045435	1.52	
9	1	1.5	4	45	55						2		0.1									B291227	202.69	204.22	3.640		VA05045435	1.53	
15	1	1	6	35	50					0.1	1.0											B291228	204.22	205.74	2.170		VA05045435	1.52	
15	1	1	6	35	50					0.1	1.0											B291229	204.22	205.74	2.350	PD/CA	VA05045435	1.52	
																						B291230	STANDARD 4D		0.459	4D	VA05045435		
12	1	0.5	6	45	50						0.1											B291231	205.74	207.26	2.190		VA05045435	1.52	
5	1	3	7	60					1.0			3.0	0.2									B291232	207.26	207.94	0.543		VA05045435	0.68	
																						B291233	207.94	208.56	2.290		VA05045435	0.62	
4	1	0.2	0.8	35		4	q	4			5											B291234	208.56	208.79	0.814		VA05045435	0.23	
3	1	2	4.5						1.0	3.0								50				B291235	208.79	209.69	2.340		VA05045435	0.90	
																						B291236	BLANK		<0.005		VA05045435		
1	1	2	2	45																		B291237	209.69	210.39	5.080		VA05045435	0.70	
2	1	1	2	45									0.2									B291238	210.39	211.13	0.553		VA05045435	0.74	
																												0.00	
1	1	1	1	45																		B291239	211.13	212.14	0.989		VA05045435	1.01	
1.0	1.0	2.0	2.0	50.0							3		1.0									B291240	212.14	212.90	0.429		VA05045435	0.76	

DRILL HOLE #: DG05-276C

FeOx: 0 = Unoxidized, 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered
Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		212.90	213.36	More clay alteration, broken up core		1	3	2		
10		213.36	213.76	Slightly altered GND contains dissem. py. and cpy			1			
10		213.76	213.99	15cm altered zone. bleached, possible silicified. Abundant po ~5%						3
10		213.99	214.88	Unalt'd GND w/ disseminated aspy. Vein @ 214.06m, 1cm milky white qtz vein @ 50° to CA, 0.2% aspy in vein. Vein at 214.16m, 1cm milky white qtz vein @ 50° to CA, 3% po in vein.						
10		214.88	216.41	Unaltered GND. Vein@ 215.01m, 1cm, white qtz @ 60° , 5% sulphides. Vein @ 215.08m, 3cm, white qtz, @ 50°, 1% aspy in margins, 3% po and 1% cpy in vein. Veinlets at 215.47, 215.68 & 215.89m, 1% po in margins. Vein @ 216.21m, 1.5cm, white qtz, @45° to CA, 3% po in vein.						
10		216.41	217.30	GND w/ chlorite alteration around veins. Veins @ 216.56, 216.68 and 216.89m: 1cm white qtz, @60° to CA, sheeted set. 10-15% po in veins. Vein @ 217.03m, 0.2cm grey qtz at 30° to CA, 2cm selvage, 3%po, 1%cpy in vein.			2			
10		217.30	218.02	GND is fractured and altered to clay within. Minor chlorite alteration also present. Vein @ 217.39m, 1cm white qtz, @50° , 3% aspy in vein, 2cm chl selvage. Broken vein @ 217.70m, ~1cm white-milky qtz.		1	1	1		
10		218.02	218.48	Unaltered GND. Veinlets @ 217.42, 217.53 & 217.63m, 0.2cm white qtz, 5-10% po in chloritic selvages						
10		218.48	219.46	Slightly chloritized GND (1), more pronounced in vein selvages. Carbonate veins intrude fractures and qtz vein throughout interval. Vein @218.58m, 0.5cm milky calcitic qtz, @50° to CA, 2cm chloritized selvage, 1% aspy in vein. Calcite-filled fracture @218.72-218.85m.			1			
10		219.46	220.20	Weak chl alt'n in GND. Veins have strong (4) chl alt in selvages. vein @ 219.63m, 1cm milky white qtz @50° to CA, 2cm chloritic selvage, 1% py in vein, 0.2% aspy in selvage. Vein @219.67m, 0.5cm, @50° to CA, 3% po in vein. Vein @ 219.87m, 1cm qtz with carbonate filled fractures at 50°, 3% py in vein and margin. Vein @ 220.11m, 1cm milky white qtz @ 50° to CA, 3% py.			1			
10		220.20	221.08	Weak to mod (2-3) chl alteration. Veins at 220.30, 220.32 & 220.36m, 0.5cm milky white qtz @ 55° to CA, 1% aspy in veins, 1cm chl selvages. Calcite-filled fractures present.			3			
10		221.08	221.40	Unaltered GND. Vein @221.35m, 0.5cm milky white qtz, @45° to CA, 5% aspy and 6% po in vein.						
10		221.40	222.50	Strong chl alteration and carb replacement/ intrusions. Carbonate shows no preferred orientation. Dissem aspy. Vein @ 331.49m, 1cm milky white qtz @ 75° to CA, no visible sulphides.			4			
10		222.50	223.28	Same as above. Aspy present in veinlets. Fractures showing no preferred orientation and are filled with aspy (90% ox'd). Disseminated aspy also present.						
10		223.28	224.03	Unaltered GND. Vein @223.32m & 223.33m, 1cm grey qtz @ 55°, 15% po in veins. Vein @ 223.84m, 0.5cm grey qtz @ 50°, 20% po in vein. Vein @223.93m, 0.5cm, grey qtz @ 50°, 1% py in vein.						
10		224.03	225.55	Unaltered GND. Vein @ 224.30m, 0.5cm grey qtz at 110°, 1% py, 20% ox'd. Vein @224.73m, 0.5cm grey qtz w/ calcite, @ 60°, 1% po in vein. Vein @ 225.09m, 1cm milky white qtz with carbonate, 3% po. Vein @225.29m, 0.5cm milky white, 5% po in vein. Broken grey qtz vein @ 225.50m. broken qtz vein @ 225.50						
10		225.55	227.08	Unaltered GND. Veinlets @ 225.70 & 225.83m, 0.2cm, milky white qtz @65° to CA, 1% po. Vein @ 225.91m, 1cm, grey qtz, @ 65° to CA, 1cm chloritic selvage, 1% aspy in vein selvage. Vein @ 226.17m, 1cm grey qtz @ 55° to CA, 1% aspy in vein selvage, 20% ox'd. Vein @ 226.45m, 0.5cm, grey qtz, @55° to CA, 3% po in vein.						
10		227.08	228.60	Unaltered GND. Vein selvages are chloritic. Vein @227.20m, 0.5cm, grey qtz @ 55° to CA, 0-2% po. Veinlets from 227.28-227.48m, 6 milky white qtz with 1 3% po. Vein @ 227.78m, 2cm grey qtz, @55°, 2% aspy in vein. Veins @ 228.01 & 228.05m, 0.5cm grey qtz @ 65° to CA, 5-10% po in vein. Vein @ 228.46m, 1cm, grey qtz @ 60° to CA, 1% aspy in selvage. Vein @ 228.54m, 0.2cm, qtz and carbonate, @55°, 5% py in vein.						
10		228.60	229.45	Unaltered GND. Veinlets present throughout. Vein @ 229.30m, 1.5cm milky white qtz @ 60°, broken, with 3% po.						
10		229.45	230.12	Weakly chloritized GND. Core is broken up. Disseminated aspy throughout core and veinlets. Vein @229.98m, 1cm, grey qtz @ 60° to CA, 1% aspy in vein.			1			
10		230.12	230.76	Unaltered GND. Sheeted vein set: Veins @ 230.18, 230.32, 230.45, 230.50 & 230.66m. 0.2cm, grey qtz, @50°, 2% aspy in margins, 1% py in veins						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n
Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B291241	212.90	213.36	0.136		VA05045435	0.46	
																						B291242	212.90	213.36	0.103	DUP	VA05045435	0.46	
																						B291243	213.36	213.76	3.430		VA05045435	0.40	
																						B291244	213.76	213.99	1.050		VA05045435	0.23	
2.0	1.0	1.0	2.0	50.0							3		0.2									B291245	213.99	214.88	0.468		VA05045435	0.89	
3.0	1.0	3.0	5.5	50.0							3	1.0	1.0									B291246	214.88	216.41	0.191		VA05045435	1.53	
4.0	1.0	1.0	3.2	60.0		2	chl	3			15	1.0										B291247	216.41	217.30	0.336		VA05045435	0.89	
2.0	1.0	1.0	2.0	50.0		2	chl	4					3.0									B291248	217.30	218.02	0.424		VA05045435	0.72	
2.0	1.0	1.0	2.0	50.0		2	chl	4					3.0									B291249	217.30	218.02	0.882	PD/CA	VA05045435	0.72	
																						B291250	STANDARD 4D		0.451	4D	VA05045435		
3.0	1.0	0.2	0.6			1	chl	4			10											B291251	218.02	218.48	0.923		VA05045435	0.46	
1.0	3.0	0.5	0.5	50.0		2	chl	4					1.0									B291252	218.48	219.46	0.553		VA05045435	0.98	
4.0	3.0	1.0	45.0	50.0		2	chl	4	1.0	3.0	3		0.2									B291253	219.46	220.20	1.210		VA05045435	0.74	
3.0	1.0	0.8	1.5	50.0		1	chl	3	1.0				1.0									B291254	220.20	221.08	0.410		VA05045435	0.88	
1.0	1.0	0.5	0.5	45.0						5			6									B291255	221.08	221.40	0.333		VA05045435	0.32	
																						B291256	BLANK		<0.005		VA05045435		
1.0	1.0	1.0	1.0	50.0																		B291257	221.40	222.50	0.224		VA05045435	1.10	
6	1	0.2	1.2	50					3				10.0									B291258	222.50	223.28	0.274		VA05045435	0.78	
3.0	1.0	1.0	2.0	55.0							20											B291259	223.28	224.03	1.310		VA05045435	0.75	
3.0	3.0	1.0	2.0	60.0							5											B291260	224.03	225.55	0.470		VA05045435	1.52	
3.0	1.0	1.0	5.0	55.0							3		1.0									B291261	225.55	227.08	0.254		VA05045435	1.53	
3.0	1.0	1.0	5.0	55.0							3		1.0									B291262	225.55	227.08	0.169	DUP	VA05045435	1.53	
3	1	2	3	55	65	2	chl	4	1		10		2.0									B291263	227.08	228.60	0.314		VA05045435	1.52	
1	1	1.5	1.5	60							3											B291264	228.60	229.45	1.070		VA05045435	0.85	
1	1	1	1	60									1									B291265	229.45	230.12	0.309		VA05045435	0.67	
5	1	0.2	1	50						1			2									B291266	230.12	230.76	1.460		VA05045435	0.64	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 19 of 22		
DRILL HOLE #: DG05-276C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:		Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		230.76	232.10	GND relatively unaltered except for ~1cm selvages around 0.2cm clear qtz veins, at: 231.01, 231.05 (40°), 231.22 (40°), 231.25 (50°), 231.29 (115°), 231.33 (70°), 231.56 (70°), 231.60 (55°), 231.86 (55°), and 231.91 (60°). Surrounding the clear qtz is milky white siliceous material. There are also planes of siliceous (bleached) GND. Sulphides conc. within clear qtz or silicified areas. Conc of po @ 231.78m (10% of 1cm silicified zone).	1	2	1	1		
10		232.10	233.61	Same rock as above. Qtz veins @ 232.15 (130°), 232.29 (60°), 232.39 (60°), *232.51 (60°), *232.67 (60°), *232.86 (60°), 233.02 (45°), 233.11 (45°). Veins with * contain ~5% po. Also present in this interval are low-angle milky qtz/ ser veins.	1	2	1	1		
10		233.61	234.05	Zone of chl/ser GND. Vein at 233.82m, only 0.2cm qtz clearly visible. Surrounding rock is silicified. Po and aspy disseminated w/in 1cm of qtz. 1cm gouge zone @ 233.94m (has <2% carbonate). Silicified zone at 233.88 has po & aspy.		3	2	1	1	
10		234.05	234.15	Zone of shear and high percentage of sulphides. Highly sericitized to show good slickenside lineation on broken face - approx. perpendicular to CA, also slickens in py. Zone is v. fine-grained ox'd py in thin laminations.	3	4	2	1	1	
10		234.15	234.56	GND altered intensely - ser/chl. Only qtz grains barely visible with no real structure. Clay alteration results in break at 234.30m. At 234.56m, one small qtz vein w/ ~15% aspy ends alteration zone.	1	4	3	1	1	
10		234.56	235.70	Unaltered GND except around 0.5-1.5cm wide qtz veins, at: 234.75 (45°), 234.84 (130°), 235.05 (20°), 235.10 (70°), 235.30 (45°). Sulphides concentrated at edges of veins throughout section in random orientations, but close to 90° to CA.		1	1		1	
10		235.70	236.90	First 20cm altered ser/chl between 2 qtz veins; then unalt'd GND btwn 0.5-1.0cm qtz veins @70° to CA, at: 236.0, 236.08, 236.28, 236.46, 236.74, and 236.91m. Also: regular fracturing @ 45° approx. every 15cm.	1	2	2			
10		236.90	237.35	Moderately chl/ser alt'd GND grades to gouge/ completely sericitized section 17cm long. Two qtz veins: at 237.06 & 237.16m, 1cm and 0.5cm thick, run at 50° to CA. Po + aspy (trace) seen at margins.	1	3	2	2		
10		237.35	238.92	Unaltered GND in between milky qtz veins. Vein @ 237.42m, 45°, 1cm, w/ cpy and po. Vein @237.45m, at 45°, 0.5cm, with aspy. Vein @ 238.6m, to 45°, 3.5cm, with po.	1	1	1			
10		238.92	239.44	Unaltered GND in between milky qtz veins. Bleached (silicified) section @ 239.35m, at 30° to CA, 2.5cm thick, 3% po. Carbonate veinlets to 25° have 0.5cm selvages.	1	1			1	
10		239.44	240.85	Ser/chl altered GND. More broken rock, crumbly, sericitic (clay) pervasive to 240.0m. Qtz veins: @239.5m, 40°, 0.4cm; @239.9m, 45°, 0.3cm; @240.1m, 70°, 0.2cm; @240.23m, 45°, 1.5cm (po, trace); @240.59m, 70°, 0.5cm (aspy, trace). Gouge section 1.5cm wide at 239.5m, to 130°. Unalt'd GND after 240.0m, except veins.	2	3	1		2	
10		240.85	242.35	More altered GND due to increase in carb veinlets in random orientations and calcite veinlet to veins at low angle (20°) to CA. One 2cm wide calcite vein @ 241.63m has geode-like quality (calcite crystallized into open space), 2cm wide, at 20° to CA, reaching to 241.85m. Qtz veins also present, overprinted by and fractured at calcite veins. Qtz veins: @241.24m, 45°, 1.5cm, 2% po; @241.64m, 2° (parallel to CA), 1.2cm, tr aspy; @241.90m, 40°, 1.2cm, 5% aspy; @242.0m, 45°, 0.5cm, 10% po.	1	2			4	
10		242.35	243.84	Chl/ser/cab altered GND; no linear features can be distinguished because of alteration. Some sections of bleached rock were likely sites of qtz veins and have disseminated aspy & po surrounding them, at 242.6m, 242.85m & 243.5m. At 243.78m, a 0.5cm vein of oxidized py denotes a shear plane w/ slickenside lineations in clay minerals. Alteration halo is 6cm wide on either side.	1	4	3	1	3	
10		243.84	244.53	Barely altered GND with 5 qtz veins: @ 243.97m, 25°, 0.5cm, tr ox'd po; @ 244.08m, 70°-20°, 1cm, 5% po, tr cpy; @ 244.14m, 30°, 0.5cm, no sulphs, @ 244.18m, 20°, 1.5cm, trace py; @ 244.28m, 20°, 1.2cm, no sulphs. Slickenside sericite on frac faces. Reg fracture angles are 55° and 145°.		2	1		1	
10		244.53	244.71	Zone of greater alteration. Remnant of qtz vein 2cm long visible. Fracture to 30° shows slicken lineation of sericite + py (5%); ser is powdery (clay alt'n). High conc of carbonate veinlets (random orientations)	1	4	2	1	3	
10		244.71	246.37	Unaltered GND w/ qtz veins (3mm, clear w/ milky edge). Veins: @244.77m, 15°, 0.5cm, 2% diss po; @245.48m, 30°, 1cm, tr po, 2% aspy; @245.82m, 40°, 1cm, 5% diss po. Bleached zone @246.26m contains ~10% po and 2% aspy. Xenolith 1cm by 4.5cm long at 245.76m parallel to C.A. Monazite; has conc of bt outside its rim in GND.	1	2	1		1	

DRILL LOG LEGEND P2

Date: May 23 to 27th, 2005

PAGE 20 of 22

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	CSV	Width (m)	VA05045076 Return Au
						Selvages												Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
10	1	0.3	20	45	115						10	1.0										B291267	230.76	232.10	2.690		VA05045435	1.34	
3	1	1.5	5			0.5	s/q				10											B291268	232.10	233.61	11.850		VA05045435	1.51	
7	1	1.5	5			0.5	s/q				0																		
3	1	1.5	5			0.5	s/q				10											B291269	232.10	233.61	11.450	PD/CA	VA05045435	1.51	
7	1	1.5	5			0.5	s/q				0																		
																						B291270	STANDARD 5E		1.370	5E	VA05045435		
2	1	0.5	1	50		10	s/chl	3	0		5		5									B291271	233.61	234.05	0.312		VA05045435	0.44	
0										5		5	5					4				B291272	234.05	234.15	3.390		VA05045435	0.10	
1	1	0.2	0.2	43		1	s/q	1					15									B291273	234.15	234.58	0.059		VA05045435	0.41	
5	1	1.5	4	45	130.0	1	s/q	1		2		0.1										B291274	234.56	235.70	0.922		VA05045435	1.14	
6	1	1	4	70		10	s/chl	2		2			0.1									B291275	235.70	236.90	0.442		VA05045435	1.20	
																						B291276	BLANK		<0.005		VA05045435		
2	1	1	1.5	50		10	s/chl	4	2		0.1		0.1									B291277	236.90	237.35	0.807		VA05045435	0.45	
3	1	3.5	5.5	45		1	chl/s	1	0		3	0.1	0.1									B291278	237.35	238.92	0.137		VA05045435	1.57	
3	4	0.1	0.3	25		0.5	cb	1	1																				
																						B291279	238.92	239.44	0.094		VA05045435	0.52	
4	1	1.5	3	45	70	0.5	5	1	1		0.1		0.1									B291280	239.44	240.85	0.261		VA05045435	1.41	
4	1	1.5	3.7	45	2.0	1.0	5	1	1		12		5									B291281	240.85	242.35	0.228		VA05045435	1.50	
1	4	2	2	20		0.2	cb	2	1				0.1																
1	4	2	2	20		0.2	cb	2	1				0.1									B291282	240.85	242.35	0.206	DUP	VA05045435	1.50	
3.0	1	1	3	45		10	s/chl/cb/q	4	1		0.1		0.1									B291283	242.35	243.84	0.797		VA05045435	1.49	
1.0	6	0.5	0.5	45		6	s/chl/cb/q	4	1	20.0								5											
5	1	1.5	4.2	20	70.0	0.3	s/q	1	0	0.1	5	0.1										B291284	243.84	244.53	0.053		VA05045435	0.69	
0										5												B291285	244.53	244.71	0.039		VA05045435	0.18	
3	1	1	2.5			0.5	chl/s/q	1	0		10		2									B291286	244.71	246.37	0.175		VA05045435	1.66	

DRILL LOG LEGEND P1	DATE: May 23 - 27th, 2005 PAGE 21 of 22	
DRILL HOLE #: DG05-276C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
		Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		246.37	247.76	GND unaltered except zone of carb+ser weathering at 246.89-246.96m. Qtz veins: @246.76m, 45°, 1cm; @247.07m, 25°, 1cm; @247.29m, 40°, 2cm, tr aspy; @247.60m, 45°, 1.5cm. No sulphides except as noted.		2	2	1	1	
10		247.76	249.08	Unaltered GND w/ qtz veins & silicified zones containing sulphides. Siliceous planes: @247.80m, 50°, 1cm, tr po; @248.18m, 50°, 1cm, tr po+aspy; @248.56m, 45°, 0.5cm, tr aspy; @248.66m, 45°, -.5cm, 20% po; @248.81m, 50°, 1.5cm, tr po. Qtz vein: @248.38m, 50°, 3cm, tr po.		1	1			
10		249.08	251.04	Unalt'd GND except qtz veins: @249.51m, 50°, 1cm, 10% aspy; @249.56m, 40°, 0.5cm, 5% po; @249.78m, 40°, 1cm, 5% po; @249.93m, 45°, 1.5cm, 10% po; @250.08m, 40°, 2cm, 5% po, tr aspy; @250.28m, 60°, 0.5cm, 5% po; @250.51m, 45°, 0.3cm, 5% po; @250.73m, 45°, 1cm, tr cpy.		1	1			
10		251.46	252.13	Altered/bleached GND, 3 large (3-4cm) qtz veins with diss sulphides, @251.90m, 252.10m, & 252.84m. Both chl and sericite pervasive and on fracs. Core has bleached/green hue and is soft. Core is interpreted as being hydrothermally altered		2	1			
10		252.13	255.79							
10		255.79	255.93	Unit of bleached sericitic GND. Core has green hue. Within middle (255.86m), a 2cm thick qtz vein @70° to CA, with 1-2% aspy, subhedral crystals; indicative of hydrothermal alteration of GND during qtz/sulphide emplacement.		2	1			
10		255.98	258.00	GND has become more mafic w/ increased amounts of biotite and qtz has become more cloudy/milky grey. Perhaps chlorite is having an effect at a microscopic level? Aspy is the predominant sulphide w/in the last several meters prior to E.O.H.						
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: May 23 to 27th, 2005

LOGGED BY: T. Croteau/M. Stone/K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)				
						Selvages												Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To		Sample Type	CSV	Width (m)	VA05045076 Return Au
4	1	2	4.5	45		0.5	s/q	1	0				0.1									B291287	246.37	247.76	**1.050**		VA05045435	1.39	
0																						B291288	247.76	249.08	**0.610**		VA05045435	1.32	
0.0																						B291289	247.76	249.08	**0.415**	PD/CA	VA05045435	1.32	
																						B291290	STANDARD 1A		**0.833**	1A	VA05045435		
8	1	2	5.8	45		0.5	s/chl/q	1	0		10	0.1	10.0									B291291	249.08	250.20	**0.555**		VA05045435	1.12	
																						B291292	250.20	251.19	**0.214**		VA05045435	0.99	
8.0	1.0	4.0	9.5	40.0						3.0			1									B291293	251.19	252.98	**1.210**		VA05045435	1.79	
5	1	0.5	1.5	45						0.1	0.1											B291294	252.98	254.51	**3.540**		VA05045435	1.53	
6	1	2	3	40.0	50.0								2.0									B291295	254.51	256.03	**1.280**		VA05045435	1.52	
																						B291296	BLANK		**0.006**		VA05045435		
1.0	1.0	2.0	2.0	70.0									2.0																
6	1	1	2	50	40						1		1									B291297	256.03	257.56	**0.092**		VA05045435	1.53	
1	1	1.5	1.5	45									1									B291298	257.56	258.00	**0.049**		VA05045435	0.44	
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-277C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1046m

BEARING: 000 | DIP: -50°

DATE STARTED: 27-May-05 | DATE COMPLETED: 01-Jun-05

COORD SYSTEM: NAD 27: EASTING: 459752 NORTHING: 7099315

COORD SYSTEM: NAD 83: EASTING: 459634 NORTHING: 7099497

NAD 27 (CORRECTED for historic grid): EASTING: 459722 NORTHING: 7099325

LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead

SECTION LINE 459722 (historic grid)

CONTRACTOR: Britton Brothers

SAMPLING DETAILS

Sample Sequence: B291299 to B291479

Requisition #: MASP448STRGOL.05Q | Date Shipped: 2-June-05

Lab Record #: VA05045437 | Date Received: 24-June-05

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 18.29m

Deviation:

Casing: 18.29m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

Duplicates:	B291302, B291322, B291342, B291362, B291382, B291402, B291422, B291442, B291462
Preparation Duplicate/ Check Assay:	B291309, B291329, B291349, B291369, B291389, B291409, B291429, B291449, B291469
Standards:	B291310(3C), B291330(6F), B291350(7G), B291370(2B), B291390(4D), B291410(4D), B291430(3C), B291450(2B), B291470(3C)
Blanks:	B291316, B291336, B291356, B291376, B291396, B291416, B291436, B291456, B291476

FROM	TO	LITHOLOGY
18.29	198.12	GND

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+ 27 Corr)
50	336.3	50.2	002.3	003.3
100	336.9	46.1	002.9	003.9
200	336.5	46.1	002.5	003.5

FROM	TO	ALTERATION
50	75	ox, ser, arg, cb
90	112	ox, ser, chl, arg, cb
125	150	ox, ser, chl, arg
162	198.12	ox, ser, chl, arg, cb

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

FROM	TO	MINERALIZATION (Veins)
50	55	aspy, py
64	75	aspy, py
93	97	aspy, py
120	127	po, aspy, py
130	140	po,aspy
167	185	po

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 1 of 12			
DRILL HOLE # : DG05-277C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-18.29			Casing						
10	18.29 - 258 (EOH)									
10		18.75	18.86	Fault gouge, clay is heavily stained by limonite, gouge contains red oxidized material, possibly hematite. Core is extremely broken and recovery is poor. Only one contact on fault can be seen. Interpreted angle of fault is @ 30° to CA.	4					
10		19.81	21.34	Within section, 2 vns, 0.75-1 cm thick of qtz @ 30-35 deg to CA can be seen. However, exact location imperceptible due to broken /poorly recovered core						
10		22.99	23.50	Core becomes sugary sand w/ heavy limonite staining, some red/brown clay (10%). no visible sulphides (difficult to constrain location due to poor core recovery). Some qtz eyes/chips are visible indicating possible veining with in section	4			1		
10		28.26	28.76	Hydrothermally altered to clay/sand. Remnant pieces of GND, sugar texture, heavy limonite staining, qtz eyes, etc. Core is severely broken, high core loss	4	2		5		1
10		28.76	35.20	no descriptions (KW)						
10		35.20	35.30	Lim stained clay zone. Zone of hydrothermal alteration as demonstrated by qtz eyes/gravel/pea-sized pieces of GND which looks to be in situ. Heavy lim, minor hematite and possible ox py.	1	2		4		1
10		36.50	37.65	Broken core; fracs w/ deep red powder (hem staining?), w/ limonite	2					
10		40.32	40.51	Clay gouge, and GND sand, qtz eyes present and clay was orange/red limonite/hematite stained indicating hydrothermal alteration either along fault surface or frac surface	2			2		
10		41.44	48.50	Possible sheeted vein system. Difficult to ascertain in areas due to core recovery and broken core, but veins appear ~ every 5 - 15cm apart and are @ 40-60 deg to CA with widths ranging from (1.5-0.5 cm) many w/ dissem aspy and po						
10		44.20	45.72	V. broken core, v. heavily encrusted by limonitic clay. Broken to sandy grvl texture.	2			3		3
10		46.05	47.00	Core appears to be silicified w/ uneven alteration of the mafics within the GND. There are sheeted clear qtz vns @ 40-45 deg to CA w/ minor diss aspy and po. Lim staining is pervasive.	3					
10		49.10	50.33	Core is extremely fractured to rubbly grvl. Heavy lim. coating. Abundant qtz pieces, possibly continuation of sheeted vn system. Section weathered to clay with some qtz eyes + mafics visible, no noticeable sulphs present.	2	1		1		5
10		50.33	51.82	Mod-Highly alt'd GND with pc's 0.1-8cm well ox'd. Relict grey qtz vn at 51.58m, 2cm wide. Totally ox'd sulphs (pyrite~5%) & hem (5%). Orientation not available (just a loose chunk).	4			1	2	
10		51.82	53.27	Increased competency, core pc's to 24cm in length. Lines of ox'd sulphs define relict qtz vns: @52.0m, 0.5cm, 35°, 15%aspy, 10%py; @52.2m, 0.4cm, 65°, 10%aspy, 5%py; @52.5m, 1.0cm, 40°, 20%aspy, 10%py; @52.6m, 0.3cm, 50°, 20%aspy, 10%py; @52.6m, 0.5cm, 50°, 5%py.	2				1	
10		53.27	53.51	Same material as 50.33m interval. No veins visible.	4			1	2	
10		53.51	54.86	Same material. One relict qtz pc. w/ ox'd py, 1cm wide, no orientation, @54.3m. Grey qtz, 1.5cm wide, 10% ox'd py @54.5m.	4			2	2	
10		54.50	54.86	Zone of extreme weathering to sand-sized particles.						
10		54.86	56.39	Same highly ox'd GND. Trace py, 90% ox'd. No veins visible.	3			1	1	
10		56.39	57.91	Red staining due to ox'd hematite on fracs. Surfaces moderately-alt'd GND. Qtz vn on 4cm$^{2\ block}$ @ 57.22m, 1.5cm wide, tr ox'd py.	3				1	

DRILL LOG LEGEND - P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	2 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																	Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
																						B291299	18.29	19.81	0.021			VA05045437	1.52	0.411
2	1	0.75	1.50	30				1		0.1			0.1									B291300	19.81	21.34	5.380			VA05045437	1.53	0.241
2	1	1.00	2.00	35				1		0.1												B291301	21.34	22.86	0.241			VA05045437	1.52	0.626
2	1	1.00	2.00	35				1		0.1												B291302	21.34	22.86	0.259	DUP		VA05045437	1.52	
1	1							1														B291303	22.86	24.38	0.623			VA05045437	1.52	
																						B291304	24.38	25.91	1.280			VA05045437	1.53	
1	1	0.25	0.25										0.1					4.0			1.0	B291305	25.91	27.43	0.475		hematite oxidation	VA05045437	1.52	
																		4.0			1.0	B291306	27.43	28.96	0.293		quartz pieces	VA05045437	1.53	
3	1	0.25	0.75	45						0.1												B291307	28.96	30.48	0.160			VA05045437	1.52	
																						B291308	30.48	32.00	0.290			VA05045437	1.52	
																						B291309	30.48	32.00	0.266	PD/CA		VA05045437	1.52	
																						B291310	STANDARD 3C		0.087	3C		VA05045437		
1	1	1.00	1.00	45	50					0.1								4.0				B291311	32.00	33.53	0.372			VA05045437	1.53	
2	1	0.25	0.50	35	60																	B291312	33.53	35.05	0.179			VA05045437	1.52	
1	1																					B291313	35.05	35.30	0.194			VA05045437	0.25	
1	1	0.20	0.20	65					2													B291314	35.3	36.58	0.100			VA05045437	1.28	
																						B291315	36.58	38.1	0.172			VA05045437	1.52	
																						B291316	BLANK		<0.005			VA05045437		
8	1	0.50	2.50	50	55				2	0.1			1.0									B291317	38.1	39.62	0.146			VA05045437	1.52	
1	1	0.50	0.50	30					1													B291318	39.62	41.15	0.144			VA05045437	1.53	
6	1	1.50	2.50	55	60						1.0											B291319	41.15	42.67	0.276			VA05045437	1.52	
																						B291320	42.67	44.2	0.221			VA05045437	1.53	
																						B291321	44.2	45.72	0.176			VA05045437	1.52	
																						B291322	44.2	45.72	1.735	DUP		VA05045437	1.52	
10	1	1.50	5.00	40	45			1					0.1									B291323	45.72	47.24	0.350			VA05045437	1.52	
3	1	1.00	1.50	30	40			1					0.1									B291324	47.24	48.77	2.190			VA05045437	1.53	
1	6	0.50	0.50										0.1									B291325	48.77	50.33	0.184			VA05045437	1.56	
2	1	2.00	2.50							5.0								5.0				B291326	50.33	51.82	0.615			VA05045437	1.49	
5	1	1.00	2.70	50	25					10.0			15.0					5.0				B291327	51.82	53.51	1.510			VA05045437	1.69	
																						B291328	53.51	54.86	3.710		Check 1	VA05045437	1.35	
																						B291329	53.51	54.86	3.990	PD/CA	Check 1	VA05045437	1.35	
																						B291330	STANDARD 6F		2.650	6F		VA05045437		
										0.1								5.0				B291331	54.86	56.39	0.238			VA05045437	1.53	
										0.1								5.0				B291332	56.39	57.91	0.796			VA05045437	1.52	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 3 of 12		
DRILL HOLE # : DG05-277C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescenc

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		57.91	59.44	Mod'ly alt'd GND. Disseminated ox'd py (2%) throughout section. Broken into avg 5cm chunks. Qtz vn relict @ 59.43m, 1cm wide, tr ox'd py. Carb (siderite/calcite) minor on weathered vnlet srfc's.	2				1	
10		59.44	60.96	Poor recovery (28%). Mod alt.	2					
10		60.96	62.48	Mod-highly alt'd GND	3			1	1	
10		62.48	64.01	Silicified zone (relict qtz vns): @ 62.69m, 1cm wide, 2% ox'd py, @62.50m, 40°, 1.5cm; @63.20m, 30°, 1cm, tr aspy.	2				1	
10		64.01	64.20	Zone of predominant qtz. Very broken up but vn appears to be >5cm wide. Ox'd py ~10%.	1				1	
10		64.20	65.53	Highly alt'd GND. 'Pure' gry qtz ~1cm thick seen @ 64.25m and 64.30m. Few low angle to CA vnlets of ox'd carb material.	3			1	1	
10		65.53	67.06	Qtz vns @ 65.57m, 0.5cm, 55°, 1-3cm selvage; @65.82m, 1cm, 50°, tr ox'd py; and @67.0m, 45°, 0.3cm, tr ox'd py. Fracture here has movement-induced orientation, shown in calcite. Highly alt'd zone follows, 2.5cm wide.	2			1	1	
10		67.06	67.25	Minor altered GND except on veinlet fractures, where aspy is 95% oxidized to black (scorodite). One qtz vn @67.15m w/ ox'd py (10%) concentrated at centre. Total width 0.5cm with 1cm selvage, at 60° to CA.	1				1	
10		67.25	68.58	Moderate to highly altered GND	2			1	1	
10		68.58	69.63	Competent core. Unaltered to minor ox'n alteration at 10cm alternating sections. Grey qtz veins @ 68.62, 68.65, 68.84, 68.91, 69.10 & 69.15m. Ox'd py (10%), and ox'd aspy - scorodite (~10%).	1	0	0	1	1	
10		69.63	70.10	Highly altered section. One piece clear quartz <1 cm in diameter amongst rubble	3			2	1	
10		70.10	71.00	Relatively competent core with quartz veinlets surrounded by oxidation (1cm selvage). Veinlets @ 70.15, 70.26, 70.42, 70.55 & 70.67m - width 0.2cm @ 40° to CA, contain 3% ox'd py and up to 20% aspy.	1			1	1	
10		71.00	71.63	Zone of intense alteration. Rubble; few subrounded, cloudy grey quartz pebbles.	3			3	1	
10		71.63	72.90	Poor recovery (50%). Moderately altered GND; broken up core. Oxidized on vein fractures. Internal structure lost to ox'n weathering	3				1	
10		72.90	73.60	Extremely weathered section. Clay texture with few quartz/GND chunks, up to 5 cm. Altered sericitically and oxidized to 71.25m where rock becomes more competent, to 15 cm lengths. Overall colour is light orange-brown.	4	2		2		
10		73.60	74.52	Orange-brown colour continues on relatively competent rock (20cm lengths max). Diss aspy 1% and ox py 15%. No relicts	5			1	2	
10		74.52	74.80	Extremely altered section, as at 72.9m. Intense scorodite in latter half (red brown to black). Core yellow, soft and granular.	5			2	1	
10		74.80	76.22	Highly altered section. Overall color is pale yellowish brown. ~15 rusty veinlets @ 90° to CA (0.1 to 0.5 cm) run through entire section and rusty patches up to 1cm in diameter speckle it. Py ~8%, diss aspy throughout, 2%. Scorodite on fractures + carbonate (siderite?). Clay minerals as well on fractures (powdery white).	5			1	2	
10		76.22	76.92	Extreme alteration in GND. Whole section is thick clay texture, pale yellowish brown to mustard yellow. Some remnants of GND: quartz eyes and powdery white clay alteration of feldspars. Carbonic alteration is not in clay, but in sandy areas. Patches of sericite with pearly lustre, ~2 cm, irregular shape.	5	2		4	1	
10		76.92	77.45	GND is broken to gravel size rubble. No visible qtz pieces to infer veining, but core recovery is poor.				5	1	1
10		77.45	78.10	Clay seem: rusty yellow, uniform, w/ qtz eyes. This indicates hydrothermal alt'n or faulting, poor recovery so interpretation is inconclusive. No visible sulphides however limonite is pervasive and coats broken core.						
10		78.10	81.33	Core is very broken. Few qtz vein pieces noted, carbonate veinlets are fracture-filling and are x-cutting each other but do not appear as pervasive. Lim coating on fractures continues to be abundant.				1	1	5
10		82.45	84.77	Sheeted vein unit. Vn's are increasing from 0.25cm to 2-4cm. Thick, milky vn's w/ dissem aspy (tr-1%) in half of vn's. Qtz vn's @ 40-50° to CA. Qtz vn's typically spaced ~10-15cm apart. Veins @ 82.91, 82.98, 83.15, 83.19, 83.24, 83.96, 84.16, 84.44, 84.47, 84.56 & 84.77m. Veins are 1-2cm thick, @40-50° to CA.						

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	4 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATEDMATERIAL														Interval						
						Selvages				Sulphides								Oxidation					Sample Number			Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other		From	To						
1	1	1.00	1.00							0.1												B291333	57.91	59.44	0.111			VA05045437	1.53	
																						B291334	59.44	60.96	0.177			VA05045437	1.52	
										0.1			0.1					5.0				B291335	60.96	62.48	0.185			VA05045437	1.52	
																						B291336	BLANK		<0.005			VA05045437		
1	1	1.00	1.00	40						0.1												B291337	62.48	64.01	0.603			VA05045437	1.53	
1	1	5.00	5.00							10.0								5.0				B291338	64.01	64.2	1.630			VA05045437	0.19	
1	1	1.00	1.00	30						0.1								5.0				B291339	64.2	65.53	0.406			VA05045437	1.33	
3	1	1.00	1.80	55	45	3.0				0.1								5.0				B291340	65.53	67.06	0.449			VA05045437	1.53	
1	1	0.50	0.50	60		1.0		5	5	10.0			10.0					5.0	5.0			B291341	67.06	67.25	0.682			VA05045437	0.19	
1	1	0.50	0.50	60		1.0		5	5	10.0			10.0					5.0	5.0			B291342	67.06	67.25	0.168	DUP		VA05045437	0.19	
																						B291343	67.25	68.58	0.040			VA05045437	1.33	
6	1	0.30	1.20	40		1.0	q/s	3	1	10.0			10.0					5.0	5.0			B291344	68.58	69.6	0.624			VA05045437	1.02	
																						B291345	69.6	70.1	0.877			VA05045437	0.5	
										3.0			20.0					4.0	1.0			B291346	70.1	71	0.430			VA05045437	0.9	
																						B291347	71	71.63	0.334			VA05045437	0.63	
																						B291348	71.63	72.9	0.211			VA05045437	1.27	
																						B291349	71.63	72.9	0.200	PD/CA		VA05045437	1.27	
																						B291350	STANDARD 7G		4.470	7G		VA05045437		
																						B291351	72.9	73.6	0.416			VA05045437	0.7	
										15.0			1.0					5.0				B291352	73.6	74.52	0.088			VA05045437	0.92	
																			4.0			B291353	74.52	74.8	0.061			VA05045437	0.28	
										8.0			2.0					5.0		3.0		B291354	74.8	76.22	0.194			VA05045437	1.42	
										5.0								5.0				B291355	76.22	76.92	0.107		ox'd py diss throughout (~5%)	VA05045437	0.7	
																						B291356	BLANK		0.022			VA05045437		
																						B291357	76.92	77.72	0.281			VA05045437	0.8	
																						B291358	77.72	79.25	0.115			VA05045437	1.53	
																						B291359	79.25	80.77	0.087			VA05045437	1.52	
2	1	0.50	1.00	30	60								0.1									B291360	80.77	82.30	0.159			VA05045437	1.53	
5	1	3.00	5.00	45	50	0.3							1.0									B291361	82.3	83.82	0.324			VA05045437	1.52	
5	1	3.00	5.00	45	50	0.3							1.0									B291362	82.3	83.82	0.207	DUP		VA05045437	1.52	
										0.1												B291363	83.82	85.34	0.339			VA05045437	1.52	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 5 of 12		
	FeOx	Ser, Chl, etc	Carbonate
DRILL HOLE # : DG05-277C	0 = Unoxidized	0 = Unaltered	0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered	5 = Strong Effervescenc

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		85.68	86.45	At 85.68m, a 2cm thick qtz/sulphide (aspy ~1%), @40-50° to CA. At 85.85m, a 1cm thick qtz vein (milky to clear) w/ trace dissem euhedral and subhedral aspy @35° to CA. At 86.13m, a 1cm thick qtz vein @40° to CA, w/ trace diss aspy (subhedral grains) along vein margins.						
10		86.45	91.55	Brkn, rubbly, gravel sized GND, no structure visible but qtz vn pieces visible w/ tr dissem aspy						
10		89.92	91.44	V. poor recovery (22%). Broken up core, ~2cm blocks, on average. Mod alt'd GND. Two qtz vein floats 1-2cm w/ ~5% ox'd py. One coherent qtz vein w/ tr aspy on margins, trace ox'd py throughout.	1				1	
10		91.44	92.96	Mod alt'd GND. Monazite xenolith. @ 91.52m. Unalt'd patches of GND show on fresh faces, shapes irregular approx 3cm in diameter. Surrounded by brown-tinted (ox'd) GND. Regular fracture angle @75° to CA. Lim staining on fract faces. Qtz veins: @92.40m, @45°, 1cm, 5% aspy throughout, tr ox'd py; @92.60m, 50°, 0.5cm, tr aspy, tr ox'd py; @93.22m, 40°, 1cm, tr aspy, tr py; @93.32m, 45°, 1.3cm, 5% aspy (margins), tr py (ox'd).	2				1	
10		92.96	93.85	Mod→high alt'd GND. Overall colour is yellowish brown except unalt'd patches ~3cm in diameter, w/ irregular boundaries. Qtz veins: @93.30m, 35°, 0.6cm, tr aspy; @93.38, 30°, 1.5cm, 5% ox'd py; @93.42, float, 1cm, 2%py; @93.58m, 120°, 1cm, 10%aspy (50% to scor), tr py (50% ox'd).	2				1	
10		93.85	94.49	Moderately alt'd GND w/ patches of unaltered, irregular edges. Section infused w/ randomly-oriented veinlets of carbonate, oxidized to limonite. Veinlet @94.15m, to 30° is >30% sulphides (ox'd py - 90%, aspy - 10%), surrounded by unalt'd GND. Qtz vein @94.45m, 50°, w/ 10% ox'd py, 0.5cm wide. Some scor w/ lim on frac faces.	2				1	
10		94.49	96.01	Seven regular fractures throughout section @30°. Qtz veins: @95.50m, 2cm, 20°, tr ox'd py, tr aspy; @95.59m, 1cm, 45°, 10% ox'd py, diss ox'd py throughout rock from 95.59-95.85m; @95.8m, 1cm, 45°, tr po, aspy; @98.85m, 0.5cm, 45°, 5% aspy.	2				1	
10		96.01	97.54	Section mod alt'd GND. Qtz vein @ 96.11m, limonite stained, to 40°, 0.5cm, w/ 5% ox'd py. More qtz veins: @96.27m, 40°, 1cm; @96.33m, 40°, 1cm; These two veins have 1cm2 patches of aspy and surface ox'n ~7% of vein. More qtz veins: @96.60m, 1cm, 30°, tr aspy, tr ox'd py; and @96.62m, 1.5cm, 55°, tr ox'd py, tr scor'd aspy.						
10		97.54	99.15	Continuation of sheeted vn unit. Veins are typically at 40-45°, spaced10-15cm apart w/ widths ranging from 0.25-1cm thick. Veins are milky white qtz, w/ trace aspy or py sulphide disseminations. Some selvages seen but do not typically indicate ox'd sulphides, perhaps vugs. Veins: @98.16m, 0.5cm veins, @40°, tr aspy; @98.53m, 0.5cm wide, @40°, tr aspy.	1	1			0	
10		99.94	100.78	Clay alt'd GND (possible fault acting as fluid conduit). Core is severely alt'd w/ "bb sized" qtz eyes, and small sand-sized pieces of unalt'd GND, all of which are heavily lim-stained, both on surface and pervasively. Some indication of quartz veining from pieces. Clay is yellow/rust-coloured. No visible sulphides.	2	1		5		1
10		100.78	103.00	At 102.49m, a 1cm vein @35° to CA; qtz/carb vein - carb on margins, qtz 0.25-0.3cm thick within center, carrying dissem aspy (trace).		1			2	
10		103.00	109.21	From 103.0m onward, core demonstrates an obvious reduction in limonite (but still on fractures), increased competency, recovery notably higher. At 105.10m, **possible gold location**: a 2cm thick qtz vein @40° to CA, with minor pervasive limonite staining has a very faint grey qtz vein w/ py x-cutting @15-20° to CA. Sulphides noted are within the 20° vein, not in the 40° one. The 20° and 50° dip of hole makes 70° to surface which may be the gold source. The vein @ 20° was v. subtle. At 105.24m, first appearance of ox'd po dissems w/in qtz vns @50° to CA. @108.14m, a 7.5cm qtz vein at 35° to CA.	2					

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides		
		OGGED BY: M. Stone/T. Croteau/ K. Whitehead	6 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides								Oxidation					Sample Number	Interval		Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
7	6	2.50	6.00	35	40								1.0									B291364	85.34	86.87	1.095			VA05045437	1.53	
3	1	0.50		40	45								0.1									B291365	86.87	88.39	0.660			VA05045437	1.52	
1	1												1.0									B291366	88.39	89.92	0.708			VA05045437	1.53	
3	1	2.00	4.00	45		2.0	q	2	2				0.1					2.0				B291367	89.92	91.44	0.230			VA05045437	1.52	
4	1	1.30	3.80	45		0.5	q	2	2	0.1			5.0					2.0				B291368	91.44	92.96	0.101			VA05045437	1.52	
4	1	1.30	3.80	45		0.5	q	2	2	0.1			5.0					2.0				B291369	91.44	92.96	0.140	PD/CA		VA05045437	1.52	
																						B291370	STANDARD 2B		3.030	2B		VA05045437		
3	1	1.50	4.10	30		2.0	q/s	3	2	2.0			5.0					2.0	2.0			B291371	92.96	93.85	0.389		%ages noted are maximum s	VA05045437	0.89	
1	1	0.50	0.50	50		1.0	q/s	1	1	10.0								5.0				B291372	93.85	94.49	0.771			VA05045437	0.64	
1	6	0.50	0.50	30		1.0	q			20.0			10.0					2.0	1.0											
4	1	2.00	4.50	45	25	1.0	q	1		20.0	0.1		5.0					3.0	1.0			B291373	94.49	96.01	0.458		%ages noted are maximum s	VA05045437	1.52	
5	1	1.50	6.00	40						0.1			1.0					0.1	0.1			B291374	96.01	97.54	0.122			VA05045437	1.53	
4	1	0.50	1.50	40		0.3	1		1				0.1									B291375	97.54	99.06	0.296			VA05045437	1.52	
																						B291376	BLANK		0.016			VA05045437		
																						B291377	99.06	99.94	0.167			VA05045437	0.88	
																						B291378	99.94	100.78	0.589			VA05045437	0.84	
1	3	1.00	1.00	35									0.1									B291379	100.78	102.11	0.101			VA05045437	1.33	
4	1	1.00	1.50	30	45								0.1									B291380	102.11	103.63	0.375		vein count includes sulph veins	VA05045437	1.52	
7	1	1.00	4.00	45	40					0.1												B291381	103.63	105.16	0.123		vein count includes sulph veins	VA05045437	1.53	
7	1	1.00	4.00	45	40					0.1												B291382	103.63	105.16	0.123	DUP		VA05045437	1.53	
3	1	0.25	0.75	25	35								0.1									B291383	105.16	106.68	0.366			VA05045437	1.52	
5	1	7.50	10.00	40	35						1.0											B291384	106.68	108.20	0.435			VA05045437	1.52	
5	1	0.50	2.00	40	50								0.1									B291385	108.20	109.21	0.126			VA05045437	1.01	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 7 of 12			
DRILL HOLE # : DG05-277C	FeOx	Ser, Chl, etc		Carbonate
	0 = Unoxidized	0 = Unaltered		0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered		5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		109.21	109.94	Alt'd GND. Brown/tan/rust colour. Mafics absent and replaced abundantly, with sericite and chlorite. Limonite is pervasive and on fractures, sulphides partially ox'd, where visible.	2	2	1		1	
10		109.60	110.80	Same as above, however several 1.5cm qtz veins are running within beginning and end of unit. @ 109.79, 109.90, 109.99, 110.14 & 110.24m, 0.5-1cm thick milky qtz vns, @35° to CA, w/ tr dissem aspy. @110.78, a 7cm milky qtz vein @35° to CA.						
10		110.80	111.94	no descriptions (KW)						
10		111.94	112.06	V. fine, uniform, brown clay seam, looks like chocolate ice cream. 100% clay.				5		
10		112.06	119.91	no description (KW)						
10		119.91	120.40	Slightly alt'd GND, pervasive limonite on fractures. Good recovery. Veinlets @120.08m, to 55°, 20%py.	1	1				
10		120.40	121.92	Unaltered GND with limonite in fractures. Qtz vein @ 120.51m, 3cm, milky white, 35°, 20%po. Vein @121.46m, 1cm, milky white, @45°, 20%po, 5%aspy in vein						
10		121.92	123.44	Lim pervasive in fractures. Qtz veins: @121.98m, 50°, 1cm, grey qtz, 5%po in veins; @122.39m, 50°, 1cm grey qtz, 10%po in vein; @122.46m, 50°, 1cm grey qtz, 5%po in vein; @122.92m, 45°, 1cm grey qtz, 5%po in vein; @123.44m, 50°, 1cm grey qtz, 10%po. Veinlets throughout section w/ 10%po and 5%aspy.	0					
10		123.44	124.20	Pervasive lim in fract. Moderately ox'd around veins. Veins: @123.61m, 1cm at 35°, milky white qtz, 1%aspy in margin; @123.73m, 2cm at 55°, grey qtz, 10%py in vein; @123.78m, 3cm at 55°, grey qtz, 5%py; @123.95m, 2cm at 55°, grey qtz, 20%po; @124.05m, 1cm at 55°, grey qtz, 10%po in vein, 5%aspy in margin.	0					
10		124.20	124.46	10cm qtz vein at 50°, 0.1% moly in vein. 10%py in smaller veins at 60°, cut by larger or may be offshoots.	0					
10		124.46	124.97	Mod'ly alt'd GND, pervasive lim in fractures, core is broken up. Vein @124.22m, 4cm grey qtz, at 35°, 1%aspy in margins. @120.66m and 120.83m, 1cm grey qtz at 35°.	3	2				
10		124.97	125.77	Mod alt'd GND. Vein @125.49m, 1cm milky white at 30°. No sulphides.	3	2				
10		125.77	126.98	Slightly alt'd GND. Veinlets common at 55°, 5%py. Vein @125.97m, 2cm grey qtz at 55°, 1% aspy in margins, 5% py in vein.	1	1				
10		126.98	127.57	Mod alt'd around fractures and veinlets at 60°, 5% aspy in veinlet selvage.	3	2				
10		127.57	128.02	3cm qtz vein at 55°. Grey, with 1%aspy in margin. Trends to zone of high alt'n. Clay rich with qtz eyes and GND fragments. Possibly hydrothermal alt'n or shear zone. Qtz vein near zone is fractured and offset in multiple locations - microfaults. @127.80m, 3cm zone of gouge, at 40° to CA, contains fragments of qtz vein, possible fault.	2	2	1			
10		128.02	128.45	Broken, altered GND. @128.27m, broken qtz veins in sugary GND; possible fault. @128.18m, GND alters to clay. Qtz eyes present with GND fragments - possibly hydrothermal. Vein @128.38m, 2cm grey qtz at 45°. No visible sulphides.	3	1				
10		128.45	129.54	Fractured GND w/ lim on fracts. Vein @129.05m, 1cm grey qtz at 50°, 3%aspy in vein, 80%oxidized.	1					
10		129.54	130.08	Slightly to mod'ly alt'd GND w/ disseminated aspy. Vein @129.79m, 2cm grey qtz at 35°, 3%py in vein, 1%aspy in margins.	1					

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	5 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																								
						Selvages				Sulphides									Oxidation					Sample Number	Interval		Au (g/T)				
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To				CSV	Width (m)	VA05045076 Return Samples
2	6	3.50	5.00	50									0.1									B291386	109.21	109.73	2.070			VA05045437	0.52	
7	1	7.50	13.00	30	45								0.1									B291387	109.73	110.85	2.670			VA05045437	1.12	
																						B291388	110.85	112.78	0.095			VA05045437	1.93	
																						B291389	110.85	112.78	0.100	PD/CA		VA05045437	1.93	
																						B291390	STANDARD 4D		0.422	4D		VA05045437		
4	1	1.00	1.50	25	35								0.1									B291391	112.78	114.3	0.195			VA05045437	1.52	
2	1	0.25	0.50	30																		B291392	114.3	115.82	0.070			VA05045437	1.52	
3	1	1.50	2.00	40									0.1									B291393	115.82	117.35	0.125			VA05045437	1.53	
5	1	1.50	3.00	30		0.1	2				0.1		0.1									B291394	117.35	118.87	0.259			VA05045437	1.52	
4	1	1.00	2.00	30		0.1	2						0.1									B291395	118.87	120.4	0.151			VA05045437	1.53	
																						B291396	BLANK		<0.005			VA05045437		
5	1	3.00	5.00	35	45	2.0	q	3	2		10.0		3.0					2.0				B291397	120.40	121.12	0.810		po in vein, aspy in selvage	VA05045437	0.72	
5	1	1.00	5.00	50	45	0.0					10.0		1.0									B291398	121.12	123.44	0.442		po in vein; aspy in margins	VA05045437	2.32	
5	1	3.00	8.00	35	55	2.0	q	2	4	10.0	10.0		1.0									B291399	123.44	124.20	1.705		po in vein; aspy in margins	VA05045437	0.76	
1	1	10.00	10.00	50		5.0	chl	4	1	10.0												B291400	124.2	124.46	0.272		10% py in veinlets, tr moly in vein	VA05045437	0.26	
3	1	4.00	6.00	35		1.0	s	4	3				1.0									B291401	124.46	124.97	0.308		aspy in margins	VA05045437	0.51	
3	1	4.00	6.00	35		1.0	s	4	3				1.0									B291402	124.46	124.97	0.609	DUP		VA05045437	0.51	
1	1	1.00	1.00	30																		B291403	124.97	125.77	0.138			VA05045437	0.8	
1	1	2.00	2.00	55						5.0			1.0									B291404	125.77	126.98	0.389		aspy in margins; py in vein; abundant veinlets at 55° w/ 5+% py	VA05045437	1.21	
																						B291405	126.98	127.57	0.040		3% aspy in veinlet selvages w/ ser/chl alt'n	VA05045437	0.59	
1	1	3.00	3.00	55		1.0	q	3	2				1.0									B291406	127.57	128.02	0.304		aspy in margins	VA05045437	0.45	
2	1	2.00	4.00	45														2.0				B291407	128.02	128.45	0.608			VA05045437	0.43	
1	1	1.00	1.00	50									10.0					3.0				B291408	128.45	129.54	0.075		aspy in vein	VA05045437	1.09	
1	1	1.00	1.00	50									10.0					3.0				B291409	128.45	129.54	0.068	PD/CA		VA05045437	1.09	
																						B291410	STANDARD 4D		0.436	4D		VA05045437		
1	1	2.00	2.00	35						3.0			1.0									B291411	129.54	130.08	0.149		py in vein, aspy in margin & diss throughout interval	VA05045437	0.54	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE 9 of 12		
	FeOx	Ser, Chl, etc	Carbonate
DRILL HOLE # : DG05-277C	0 = Unoxidized	0 = Unaltered	0 = No Effervescence
	5 = Intensely Ox'd	5 = Intensely Altered	5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		130.08	131.06	Unalt'd GND. Veins, grey qtz: @130.16m, 2cm, 30°; @130.36m, 0.5cm at 50°; 10%aspy; @130.41m, 0.2cm at 50°, 1%aspy; @130.55m, 1cm at 50°, 8%py; @130.77m, 1.5cm, at 50°, 5%py.						
10		131.06	132.59	Slightly alt'd GND, limonitic fractures. Veins: @131.38m, 0.5cm grey qtz at 60°; @131.88m, 0.3cm grey qtz @50°, 10%py, @131.95m, 0.5cm grey qtz at 50°, 5%aspy; @132.00m, 2cm grey qtz @50°, 10%aspy, 3%cpy, @132.06, 0.3cm grey qtz, 5%aspy, at 50°.	1	2				
10		132.59	134.11	Unalt'd GND; lim on fractures, veinlets running at 40°.						
10		134.11	134.81	Slightly alt'd GND. Fractures at 55°.	2	2				
10		134.81	135.64	GND is bleached; <1%bt present; disseminated aspy present		2	1			
10		135.64	136.88	Lim on fractures. GND alt'd to grey-green.		1	2			
10		136.88	138.02	Core is highly fractured and broken. Clayey gouge present @ 136.91m, 137.62m, 137.91m @ 45deg to CA. Qtz eyes and broken GND in clay - possible hydrothermal or shear	2	2		4		
10		138.02	139.52	Oxidized GND @ 138.68m becomes gouge ± GND frags. Decomposed GND: qtz eyes and frags present in clay - hydrothermal or shear	2	1		2		
10		139.52	139.98	10cm qtz vein @ 30°. Vein is fractured and shows slickensides on a 30° fracture @139.60m. 5cm qtz vein @ 30° at 139.76m.				3		
10		139.98	141.05	Unalt'd GND, oxidized @139.98m to 141.05m. At 140.75m, core is altered to rust brown, minor sericite, core is weaker, yet competent, but more easily broken	2	1	1			
10		141.05	141.73	Vein @141.37m, 1cm white qtz @30°, 5% aspy, crosscut by 0.3cm grey qtz vein at 60° to CA						
10		141.73	143.26	Unaltered GND. Veins appear to be sheeted set. Minor lim on fractures. Moly found in veining at 143.06m	0					
10		143.26	144.69	Minor lim on fractures						
10		144.69	150.78	At 148.86 a 2 cm x 5cm bleb of diorite as a xenolith within GND, no chilled margin						
10		150.78	150.88	Altered zone with 3 cm qtz vein adjacent. Contact angles at 40° to CA. Core is brown with qtz eyes as breccia within brown sericite matrix. Core is soft yet competent	1	2	1			
10		150.88	159.40	no descriptions (KW)						
10		159.40	163.50	Sheeted vn system. Veins are spaced about every 5-10cm @ 35-50° to CA, with avg thickness 1cm+ . Only recognized sulphide present is diss po, trace to 1%.						
10		163.44	164.59	Altered GND Core is stained heavily (pervasively with lim) and on fractures. Core is mod'ly broken to large gravel sizes. Chlorite prevalent in section, several 3cm veins within unit which may have been conduits of hydrothermal fluids. No visible sulphides. Contact at 163.44m is marked by a 3cm vein @ 40° to CA. The 164.59m contact is less abrupt but @40° to CA, with a marked decrease of pervasive limonite easily recognized by color change and core competency.	3	1	2	0	0	
10		164.59	166.33	GND has a noticeable decrease in veins per m, core is more broken, with lim heavy on fractures, and mod to low pervasively within GND	2	1	1			

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	10 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)				VA05045076 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To			CSV	Width (m)	
5	1	2.00	5.20	50	30					8.0			10.0									B291412	130.08	131.06	0.153		aspy in vein, py in vein	VA05045437	0.98	
5	1	2.00	3.60	50						10.0			5.0									B291413	131.06	132.59	0.192			VA05045437	1.53	
7	1	1.00	2.50	40									5.0									B291414	132.59	134.11	0.050		aspy in vein and margins	VA05045437	1.52	
1	1	0.30	0.30	65																		B291415	134.11	134.81	0.157			VA05045437	0.7	
																						B291416	BLANK		<0.005			VA05045437		
3	1	1.00	1.80	30						3.0			2.0					1.0				B291417	134.81	135.64	1.065		diss aspy present in core	VA05045437	0.83	
0																						B291418	135.64	136.88	0.424			VA05045437	1.24	
1	1	2.00	2.00	50									1.0								2.0	B291419	136.88	138.02	0.151			VA05045437	1.14	
																						B291420	138.02	139.5	0.650			VA05045437	1.48	
2	1	10.00	15.00	30									20.0									B291421	139.5	139.98	9.070		aspy present in vein	VA05045437	0.48	
2	1	10.00	15.00	30									20.0									B291422	139.5	139.98	22.300	DUP		VA05045437	0.48	
4	1	1.00	3.00	45	50	2.0		3	1	5.0			10.0									B291423	139.98	141.05	1.920		Aspy in selvage, py in veins	VA05045437	1.07	
3	1	1.00	1.90	30	60								10.0									B291424	141.05	141.73	0.325		Aspy in vein and selvage	VA05045437	0.68	
5	1	1.00	2.20	35	50	1.0	q	2	1		10.0		1.0									B291425	141.73	143.26	0.031		Po found with moly in vein @ 143.06 5% moly in vein	VA05045437	1.53	
5	1	1.00	2.10	40		1.0	q	2	1		5.0		1.0									B291426	143.26	144.69	0.019		Po in vein, aspy in margin	VA05045437	1.43	
8	6	0.25	3.00	42	30	0.3		1			1.0											B291427	144.69	146.3	0.026			VA05045437	1.61	
4	1	1.00	2.00	20	35	0.5		1			0.1											B291428	146.3	147.83	0.297			VA05045437	1.53	
4	1	1.00	2.00	20	35	0.5		1			0.1											B291429	146.3	147.83	0.144	PD/CA		VA05045437	1.53	
																						B291430	STANDARD 3C		0.077	3C		VA05045437		
4	1	1.50	7.00	30	40						1.0											B291431	147.83	149.35	0.057			VA05045437	1.52	
8	1	3.00	9.00	30	45	0.3		1			0.1		0.1									B291432	149.35	150.88	0.049			VA05045437	1.53	
5	1	1.00	2.75	40	50	0.3		1					1.0									B291433	150.88	152.4	0.060			VA05045437	1.52	
10	6	1.00	10.00	35	40	0.3		1			2.0											B291434	152.4	153.90	0.066			VA05045437	1.5	
4	1	3.00	4.25	40		0.2		1			0.1											B291435	153.9	155.45	0.041			VA05045437	1.55	
																						B291436	BLANK		<0.005			VA05045437		
6	1	2.00	7.00	45	30	0.2		1														B291437	155.45	156.97	0.301			VA05045437	1.52	
5	1	0.50	5.00	40							1.0											B291438	156.97	158.5	0.039			VA05045437	1.53	
3	1	6.50	8.00	30	40						1.0											B291439	158.5	160.02	1.055			VA05045437	1.52	
9	1	3.00	10.00	32.5	40	0.2		1			1.0											B291440	160.02	161.54	0.189			VA05045437	1.52	
10	1	3.00	17.00	30	40	0.2		1			1.0											B291441	161.54	163.44	0.820			VA05045437	1.9	
10	1	3.00	17.00	30	40	0.2		1			1.0											B291442	161.54	163.44	0.280	DUP		VA05045437	1.9	
3	1	3.00	7.00	40						0.1												B291443	163.44	164.59	0.096			VA05045437	1.15	
2	1	1.50	2.00	45	50	0.3		1	2													B291444	164.59	166.12	0.040			VA05045437	1.53	
4	1	1.00	6.00	35	50	0.1		1			0.1							1.0				B291445	166.12	167.64	0.070			VA05045437	1.52	
2	1	0.25	0.50	30	40	4.0		3			0.1											B291446	167.64	169.16	0.090			VA05045437	1.52	
2	1	0.50	1.25	35	45						1.0							1.0				B291447	169.16	170.69	0.589			VA05045437	1.53	

DRILL LOG LEGEND P1	DATE: May 27 - June 1, 2005 PAGE \\ of 12		
DRILL HOLE # : DG05-277C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescenc

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		170.69	171.15	Chloritized, altered GND. Core is green/brown with sericite, mod soft. @170.69m, core abruptly alters with initial pervasive lim progressing to chloritization. Contact occurs parallel to central vein in unit @45° to CA. Diss aspy with vein and surrounding 10-15cm of GND (~1%).	3	2	2	0	0	
10		171.15	172.20	Lim stained core decreasing with lim only on fractures @172.20m.	1	1	0			
10		172.21	173.74	Zone of high alteration, colour orangey brown. Reg. fractures at 35° (8), limonite pervasive. Tonalite xenolith at 172.6m, approx. 2 by 5cm.	2			1	1	
10		173.74	175.26	Mod'ly alt'd GND. 1cm^2 xeno of tonalite within largest quartz vein at 174.56m.	2			1		
10		175.26	176.26	Highly alt'd GND. Fractured, colour orangey brown.	2	1		1		
10		176.26	176.78	Wide zone of qtz - 24cm. Crosscut by veinlets filled with lim (176.26m to 176.50m).	1	1				
10		176.78	177.44	Unaltered GND	0	1	1			
10		177.44	178.31	Unaltered GND w/ qtz veins	0	2	1			
10		178.31	179.83	Unaltered GND	0					
10		179.83	180.81	Altered patch, 5 by 8cm, green coloured, irregular edges, 2%po						
10		180.81	181.55	One large, branching qtz vein. Tonalite xeno 3cm by 6cm, rounded edges w/ 2mm reaction rim.		1			1	
10		181.55	183.00	Broken up GND (max length of core 20cm). Unaltered.	2	1			1	
10		183.00	184.40	Extremely altered GND. One branching qtz vein. Colour is yellowish-white. Rock is crumbly and clay-rich. Weak slickenside lineation shows on sericite/limonite fracture faces - shear zone.	4	3		2	2	
10		184.40	185.10	Fractures near parallel to CA infilled with limonite and sericite.	3	2		1	1	
10		185.10	185.50	Silt layer, med brown mud with ~5cm blocks of GND.	1					
10		185.50	186.68	Unaltered GND.						
10		186.68	188.80	Unaltered GND.	1	1				
10		188.08	189.31		2	2			1	
10		189.31	190.50	Unaltered to lightly altered GND	2	1			1	
10		190.50	192.02	Mod alt'd GND. Lim on fractures. Overall colour is whitish green w/ 0.5cm selvages	1	4	2		1	
10		192.02	192.88	GND as above. One qtz vein running nearly parallel to CA goes through core for 34cm, but is only 1cm wide. Shear/gouge section at 192.54m is approx. 2cm wide; altered to white clay texture.	1	4	2	1	1	
10		192.88	193.56	Extremely altered zone to 193.20m, where alt'n becomes moderate. Colour whitish-pale brown. Regular breaks parallel to CA (4).	4	3	0	1	1	
10		193.56	194.47	Mod'ly alt'd GND, as at 190.5m.	3	3	1	1	1	
10		194.47	195.51	Mod'ly alt'd GND, as at 190.5m	1	3			1	
10		195.51	196.60	Mod'ly alt'd GND, as at 190.5m	1	2				
10		196.60	198.12	Mod'ly alt'd GND, as at 190.5m; random fracture orientation	1	2				
				EOH						

DRILL LOG LEGEND P2		Date: May 27 - June 1, 2005	PAGE
Selvages	Ox. State		
0 = No Alteration	0 = No Oxidized Sulphides	LOGGED BY: M. Stone/T. Croteau/ K. Whitehead	12 of 12
5 = Intense Alt'n	5 = All Sulph Oxidized		

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATEDMATERIAL																				
						Selvages				Sulphides									Oxidation						Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)			CSV	Width (m)	VA05045076 Return Samples
3	1	3.00	4.00	45							0.1		1.0					1.0				B291448	170.69	172.21	0.060			VA05045437	1.52	
3	1	3.00	4.00	45							0.1		1.0					1.0				B291449	170.69	172.21	0.045	PD/CA		VA05045437	1.52	
																						B291450	STANDARD 2B		2.830	2B		VA05045437		
2	1	3.00	4.50	45		1.0	q	2	2	1.0								5.0				B291451	172.21	173.74	0.125			VA05045437	1.53	
9	1	2.00	8.00	45		5.0	q		3	0.1	5.0						0.1					B291452	173.74	175.26	14.900		moly	VA05045437	1.52	
2	1	1.00	2.00	40							3.0											B291453	175.26	176.26	0.068			VA05045437	1	
1	1	2.00	2.00	20							20.0		0.1					2.0												
1	1	20.00	20.00	45							5.0							2.0				B291454	176.26	176.78	0.220			VA05045437	0.52	
3	1	1.00	2.50	55		4.0	s/chl	3	1		10.0											B291455	176.78	177.78	0.094			VA05045437	1	
																						B291456	BLANK		<0.005			VA05045437		
5	1	1.00	3.00	50		0.5	s/chl	3	0		10.0	5.0							5.0			B291457	177.78	178.31	0.093			VA05045437	0.53	
3	1	1.50	2.80	30		0.4	s/q	3	0		5.0							0.0												
0																						B291458	178.31	179.83	0.041			VA05045437	1.52	
1	1	1.00	1.00	50		0.0					0.1							1.0				B291459	179.83	180.81	0.017			VA05045437	0.98	
1	1	15.00	15.00	45	15	1.0	q/s	4	0		25.0							1.0				B291460	180.81	181.55	0.052			VA05045437	0.74	
0																						B291461	181.55	183	0.019			VA05045437	1.45	
0																						B291462	181.55	183	0.024	DUP		VA05045437	1.45	
1	1	2.00	2.00	30																		B291463	183.00	184.4	0.047			VA05045437	1.4	
1	1	1.00	1.00	50		0.0																B291464	184.4	185.10	0.072			VA05045437	0.7	
0																						B291465	185.1	185.50	0.063			VA05045437	0.4	
1	1	2.00	2.00	45		0.5	q	4	0		18.0							1.0				B291466	185.5	186.68	0.103			VA05045437	1.18	
0																						B291467	186.68	188.08	0.045			VA05045437	1.4	
1	1	3.00	3.00	35		2.0	q/s	3	3	2.0	5.0							3.0				B291468	188.08	189.31	0.628			VA05045437	1.23	
1	1	3.00	3.00	35		2.0	q/s	3	3	2.0	5.0							3.0				B291469	188.08	189.31	0.717	PD/CA		VA05045437	1.23	
																						B291470	STANDARD 3C		0.081	3C		VA05045437		
1	1	1.00	1.00	45		1.0	s/q	3	1		1.0											B291471	189.31	190.5	0.025			VA05045437	1.19	
2	1	0.50	1.00	35		0.5	s/q	3	1			4.0	1.0									B291472	190.5	192.02	0.020		margins silicified	VA05045437	1.52	
1	1	1.20	1.20	50		0.0																					margins straight			
1	3	1.00	1.00	5		0.5	q/s	3	2	0.1								5.0				B291473	192.02	192.88	0.039			VA05045437	0.86	
1	1	1.00	1.00	30		1.0	q/s	3	0.5																					
0																						B291474	192.88	193.56	0.022			VA05045437	0.68	
1	3	1.00	1.00	20		0.0				0.0												B291475	193.56	194.47	0.054			VA05045437	0.91	
																						B291476	BLANK		<0.005			VA05045437		
1	1	1.20	1.20	30		0.5	cb/q	1	2	2.0	5.0						0.1					B291477	194.47	195.51	0.294		trace moly	VA05045437	1.04	
1	3	1.30	1.30	10		0.5	cb/q	3	2	0.1			0.1					5.0				B291478	195.51	196.6	0.156			VA05045437	1.09	
1	1	0.50	0.50	45						1.0	1.0											B291479	196.6	198.12	0.155			VA05045437	1.52	
1	1	3.00	3.00	30		1.0	q	1	1	2.0			0.1														aspy in selvage			
																								EOH.						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-278C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1037m

BEARING: 000 | DIP: -50°

DATE STARTED: June 1 2005 | DATE COMPLETED: June 4 2005

COORD SYSTEM: NAD 27: 459713E — EASTING: 459713 NORTHING: 7099325

COORD SYSTEM: NAD 83: 459593E — EASTING: 459593 NORTHING: 7099509

NAD 27 (CORRECTED for historic grid): — EASTING: 459783 NORTHING: 7099335

LOGGED BY: Melodie Stone, Terry Croteau, Kristian Whitehead

SECTION LINE 459675 (historic grid)

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 19.81m

Deviation:

Casing: 19.81m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B291480 to B291499 and B291500 to B291609

Requisition #: MASP44855STRGOL.05Q — Date Shipped: 8-June-05

Lab Record #: VA05045519 and VA05044876 — Date Received: 13-June-05

Sample Sequence: B291610 - B291631

Requisition #: MASP44855STRGOL.05Q — Date Shipped: 8-June-05

Lab Record #: VA05046431 — Date Received: 13-June-05

Duplicates:	B291482, B291502, B291522, B294542, B291562, B291582, B291602, B291622
Preparation Duplicate/ Check Assay:	B291489, B291509, B291529, B291549, B291569, B291589, B291609, B291629
Standards:	B291490 (4D), B291510 (3C), B291530 (3C), B291550 (5E), B291570 (3C), B291590 (2B), B291610 (5E), B291630 (7G)
Blanks:	B291496, B291516, B291536, B291556, B291576, B291596. B291616

LITHOLOGY

FROM	TO	LITHOLOGY
19.81	179.83	GND

ALTERATION

FROM	TO	ALTERATION
26.05	80.77	Ox, ser, arg, ± cb
88.24	113.08	Ox, ser, arg
164.59	178.93	Ser, chl, arg, cb

MINERALIZATION (Veins)

FROM	TO	MINERALIZATION (Veins)
60.96	85.34	Py, aspy
115.82	132.82	Py, aspy, po
164.59	167.14	Cpy, py, po
178.31	179.83	Po, py

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
50	334.7	-49.7	000.7	001.7
100	330	-50.6	356	357
179.83	16.3	-50.8	42.3	43.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Note: Data from reflex test at 179.83 is unreliable data

DRILL LOG LEGEND — P1	DATE: June 1 - 4, 2005 PAGE 1 of 8	
DRILL HOLE # : DG05-278C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1		0.00	19.81	Casing (no core recovery)						
10	19.81-20.25	19.81	20.25	GND / qtz and shale-like metasediments (argillite), gravel sized pieces. Unable to discern whether metaseds due to abundant qtz and granodiorite pieces, however contact / lithology change is proximal. The drill set-up appeared that collar was in metaseds (?). (poor core recovery / and v. broken core). I would interpret this to be the MSED/GND contact.	1					
80	**20.25-26.05**	20.25	23.60	MSED, core is v. broken w/ limonite staining on fracs and pervasive within foliations. Metaseds appear as dark brown to black, fine-grained, less than 1mm thick foliations which have suffered moderate silicification determined by the inability to scratch core with a nail. Foliations are, within the first few feet, at 45° - 55° to CA, with the appearance of foliation angles changing due to folding episodes at a local level. No visible sulphides present however minor hematite staining is observed on some pieces of core. Qtz pieces indicate that veins are both x-cutting and are on foliation. No visible sulphides within the qtz pieces noted. Core recovery is approx 40%. At ~20.50m, silicification diminishes and core becomes essentially argillite (core can now be scratched by a nail).	1					
80		23.60	25.00	From 23.60-23.74m, core becomes qtz eyed; clay gouge with yellow /brown coloring. Appears as hydrothermally altered, possible fault zone.	2	1		3		
80		25.00	26.05	From 25.00-25.91m, argillite has multiple vn sets within it and has thickness of veins ranging from 0.25 - 1cm thick, milky coloured. At 25.60m, 2 vns x-cut each other at 35° and 155-160° to CA. No visible dissem sulphides present. Limonite on fractures but less pervasive on foliation. Core section was poor core recovery but competent core pieces were available for logging.	1					
10	**26.05-65.53**	26.05	30.48	Granodiorite/argillite contact, GND continues on. Core is broken to rubbly gravel; few structural bits intact for logging, lots of qtz pieces.	1			1		
10		30.48	32.00	GND altered to sand-sized pieces. Core is not bleached, heavy limonite staining. Visible qtz pieces indicating veins present. Minor clay mostly sand, mafics easily visible. Core essentially looks weathered to rotten.	2			1		
10		32.00	33.53	Core recovery is poor and core is extremely broken, however it appears as though there is a sheeted qtz vein system occurring, due to the abundance of qtz pieces in the rubble. No visible sulphides noticed w/ in the qtz pieces. Heavy limonite on fracs and pervasive.	2			1		
10		33.53	35.20	Core recovery is very low however several episodes between gravel pieces to clay sections w/ qtz eyes w/ heavy limonite straining on fracs and pervasive. Hydrothermal alteration is evident throughout this particular section, no sulphides noted. Clay is rusty brown and uniform. Remaining core is of sandy gravel consistency.	2			2		
10		35.20	38.10							
10		38.10	39.62	Core has same characteristics as above (33.53-35.20m). Possible hematite staining on fracs.	2			1		
10		39.62	41.15							
10		41.15	44.20	Highly digested GND, mafics intact but core is abundant w/ sericite. Core is salt/pepper in appearance & crumbles when touched. No coherency. Limonite is extremely pervasive & on fracs. Minor 10-15cm units of rusty coloured clay seems very indicative of hydrothermal alt'n.	3	1		1		
10		44.20	45.72	Core becomes much more competent, but limonite on frac/selvages & is pervasive. Ox'd py w/in some vns/vnlets pieces show red rust blebs (may be well-ox'd pyrite).	1					
10		45.72	47.24	Core is extremely broken w/ poor core recovery. Core is sandy gravel in texture w/ v. abundant limonite & bits of ox'd py. Some clay seems relict.	3	1		1		
10		47.24	48.77	Core is essentially a clay gouge. Alt'n zone - Core in places is somewhat preserved, mafics are intact w/ limonite & sericite on fracs & pervasively. Qtz eyes visibly intact. Some indications of veins. Minor hematite staining & ox'd py pieces w/in qtz pieces.	3	1		3		
10		48.77	53.61	Core is extremely broken to sandy gravel or to clay seams. Core recovery is ~50-65%. Limonite is pervasive & abundant, sericite is on fracs & w/in selvages. Mafics are still intact & highly ox'd py can be seen as relict orangey-red blebs on qtz pieces & in broken pieces of core.	4	3		2		
10		53.61	55.53							
10		55.53	55.58	Clay seam w/ qtz eyes, clay is of rusty uniform color. Minor reddish staining on 55.58m contact surface indicating ox'd py (essentially an alt zone).	3	1		4		
10		55.58	55.80							
10		55.80	59.44	Core is very uniformly hydrothermally alt'd to soft, mushy, sandy clay w/ heavy pervasive limonite. Sericite is observed in relict selvages & fracs. Qtz eyes 'bb'-sized abundant. Core looks like it has been digested by meteoric waters. Some reddish blebs & stains reminiscent of former py, not a lot of visible vns. Mafics are preserved where clay is less abundant. Core loss is @ ~80%, thus good representation of actual unit.	5	3		4		
10		59.44	60.96	GND altered to clay/crumbly texture. Colour is orangey-pale brown. Aligned qtz pebbles denote old veins. Carbonate is siderite >calcite.	3	1		3	2	
10		60.96	62.48	Qtz eyes and relict feldspars left in crumbly mess. Ox'd hematite present. Sericite aligned at ~15° to CA	4	2		2	2	
10		62.48	64.01	Colour whitish yellow to orangey brown. Qtz vein at ~62.9m, grey qtz.	3	2		3	2	
10		64.01	65.41	Colour a more medium-dark brown. Crumbly-clay gouge GND. Clear-milky qtz veins	4			3	2	
10		65.41	65.53	Large qtz vein w/ lim on fractures. Diss ox'd py throughout. Ox'd hematite present ~3%	1				1	
90	**65.53-66.00**	65.53	66.00	Qtz vein at 65.53m. Section is argillite (MSED); fine mafic laminations define meta-beds. Felsic section at 65.7m (QZZ) with diss ox'd py, muscovite (15%). Microfolds visible on the cm/mm scale. Ox'd hematite (10%) in mafic sections.	4	1		4	1	
10	**66.00-179.83**	66.00	67.06	Clay to crumbly GND. Largest pieces ~2cm square. Clear qtz pebbles noted at 3 depths	4	1		3	2	
10		67.06	68.58	Highly to extremely altered GND. First 20cm is somewhat coherent core (10cm chunks). After that gouge-clay texture. More competent GND below qtz vein relict, for ~10cm. Gouge to end.	4	3		3	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2006

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.25	0.5	40	45	0.1		1														B291480	19.81	21.34	<0.005			VA05045519	1.53
2	1	0.50	1.0	35	40	0.1		1														B291481	21.34	22.86	0.005			VA05045519	1.52
2	1	0.50	1.0	35	40	0.1		1														B291482	21.34	22.86	0.014	DUP		VA05045519	1.52
1																						B291483	22.80	24.38	0.027		pieces	VA05045519	1.58
5	1	1.00	3.0	25	35	0.1		1														B291484	24.38	25.91	0.041			VA05045519	1.53
4	1	2.00	2.0	50				1														B291485	25.91	27.43	0.019			VA05045519	1.52
																						B291486	27.43	28.96	0.060			VA05045519	1.53
2	1	0.75	2.0	50		1.0																B291487	28.96	30.48	0.226		greater than 2	VA05045519	1.52
1																						B291488	30.48	32.00	0.376		qtz pieces only	VA05045519	1.52
1																						B291489	30.48	32.00	0.478	PD/CA		VA05045519	1.52
																						B291490	STANDARD 4D		0.239	4D		VA05045519	
4	1	0.75	3.0	40				2														B291491	32.00	33.53	0.972		4 and qtz pieces	VA05045519	1.53
1																						B291492	33.53	35.05	0.281		qtz pieces only	VA05045519	1.52
1																						B291493	35.06	36.58	0.470		qtz pieces only	VA05045519	1.52
3																						B291494	36.58	38.10	0.114		2 and qtz pieces	VA05045519	1.52
1																						B291495	38.10	39.62	<0.005		qtz pieces only	VA05045519	1.52
																						B291496	BLANK		0.396			VA05045519	
1																						B291497	39.62	41.15	0.843		qtz pieces only	VA05045519	1.53
2	1			35																		B291498	41.15	42.67	0.636		1 vein + qtz pieces	VA05045519	1.52
2	1			40	45	0.1		1														B291499	42.67	44.20	0.779		1 vein + qtz pieces	VA05045519	1.53
7	1	0.50	3.0	40	50	0.1		1		0.1								3.0				B291500	44.20	45.72	0.184		tr hem	VA05044876	1.52
1										0.1							0.1	3.0				B291501	45.72	47.24	0.886		tr hem; qtz pieces	VA05044876	1.52
1										0.1							0.1	3.0				B291502	45.72	47.24	0.234	DUP		VA05044876	1.52
										0.1							0.1	3.0				B291503	47.24	48.77	0.248		tr hem	VA05044876	1.53
1										0.1								2.0				B291504	48.77	50.29	0.134		qtz pieces	VA05044876	1.52
2	1			45	50					0.1								2.0				B291505	50.29	51.82	0.117		qtz pieces	VA05044876	1.53
4	1	1.50	3.0	45	50					0.1								4.0				B291506	51.82	53.34	0.302			VA05044876	1.52
2	1	1.00	1.5	55	60					0.1			0.1					4.0				B291507	53.34	54.86	0.156		qtz pieces	VA05044876	1.52
1										0.1								5.0				B291508	54.86	56.39	0.768		qtz pieces only	VA05044876	1.53
1										0.1								5.0				B291509	54.86	56.39	4.170	PD/CA		VA05044876	1.53
																						B291510	STANDARD 3C		0.091	3C		VA05044876	
										0.1								5.0				B291511	56.39	57.91	0.221		clay	VA05044876	1.52
										0.1								5.0				B291512	57.91	59.44	0.128		clay	VA05044876	1.53
										0.1								5.0									clay		
2	1	1.00	2.0	45						0.1								5.0				B291513	59.44	60.96	0.263			VA05044876	1.52
2	1	1.50	2.0	50						3.0								5.0				B291514	60.96	62.48	0.571			VA05044876	1.52
1	1	3.00	3.0	45						2.0								5.0				B291515	62.48	64.01	0.111			VA05044876	1.53
																						B291516	BLANK		<0.005			VA05044876	
2	1	2.50	3.0	50						0.1								5.0				B291517	64.01	65.41	0.358			VA05044876	1.40
1	1	12.00	12.0	45						3.0								5.0				B291518	65.41	65.53	0.166			VA05044876	0.12
1	1	5.00	5.0							7.0								5.0				B291519	65.53	66.00	1.210		pieces only, angles indeterminable	VA05044876	0.47
3	1	1.00	3.0							0.0												B291520	66.00	67.06	0.060		pieces only, angles indeterminable	VA05044876	1.06
1	1	3.00	3.0							2.0	1.0							5.0				B291521	67.06	68.58	0.092		pieces only, angles indeterminable	VA05044876	1.52

DRILL LOG LEGEND P1	DATE: June 1 - 4, 2005 PAGE 2 of 8		
DRILL HOLE # : DG05-278C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		68.58	70.10	Mod. to highly altered GND. Core coherent from 69.15m with only minor clay alt'n. Oxidation throughout. Colour pale brown.	4	3		2	2	
10		70.10	71.63	Grades from competent (but mod. altered) to highly altered GND. Diss ox'd py throughout section (one patch 1cm^2 near qtz vein)	4	4		2	2	
10		71.63	73.15	Colour orangey pale brown. Core fairly competent, recovery good (89%).	2	1		2	1	
10		73.15	79.25	Mod - highly-altered GND. Colour white-pale brown. Qtz, feldspars, and most bt still in situ with some (30%) alt'n of feldspars to clay (opaque, white) minerals. Matrix material all altered. Qtz veins overprinted by alteration, so they are broken and little to no selvage present. Qtz veins broken and selvage overprinted by alt'n.	3	2		3	1	
10		79.25	80.77	Moderately to highly altered GND trending to gouge @ 79.33-79.67m. Gouge contains decomposed GND frags and a possible remnant quartz vein. 5cm broken qtz vein @ 79.92m	2	1		2		
10		80.77	81.52	Core broken into fragments up to 6 cm, becoming more altered to sericite @81.13 -81.37m. 4cm fractured and oxidized grey qtz with carb vein @81.30m.	1	3		2		
10		81.52	82.55	Clayey gouge dominant with 9cm section of moderately altered GND @82.30m	1	2		3		
10		82.55	83.82	Slightly altered GND with lim on fracs. Core is highly fractured and broken. Fractures predominantly @ 80-85° to CA	1					
10		83.82	85.34	Moderately altered, less fractured and broken. Lim on frac. @83.71m, 2cm clayey gouge @ 45° to CA - shear.	2	1		1		
10		85.34	86.87	Less altered, becoming broken and clay rich @85.94m. Broken qtz veins present in clays, appear offset --possible small scale fault/shear.	1			3		
10		86.87	87.40	Slightly altered GND, more competent	1					
10		87.40	87.77	Zone of fractured and offset qtz veins. Offset sinistrally @50°.	1					
10		87.77	88.24	Unaltered GND trending to carb alt'n after 87.98m	0	1			3	
10		88.24	88.92	Ox'd GND. Qtz veins offset @50°, appears sinistral. Lim on fractures.	2			1		
10		88.92	91.44	Core fractured at 50°, same as the offset angle of the quartz veins						
10		91.44	94.49	Moderately altered GND with lim on fractures. GND has sugary, mushy texture with higher clay content towards end of interval. Qtz veins are fractured or broken.	2			3		
10		94.49	96.01	Intensely altered to clay from 94.49-94.79m. @94.79 ~1m shear zone. Lineation @130°. Winged porphyroblast @96.46m, parallel to lineation direction and shows a sinistral rotation, indicating shear sense. Qtz vns present are broken and sheared. Shear zone is grey-green.	2			1		
10		96.01	96.14	Clay gouge, qtz eyes present - possible hydrothermal alteration, likely related to shear zone above.	1			3		
10		96.14	96.68	Moderately altered GND	1	1		3		
10		96.68	98.28	Broken GND, lim staining, sugary texture. Qtz veins are broken.	2			3		
10		98.28	99.06	Moderately altered GND						
10		99.06	99.68	At 99.06m is a 4cm clay gouge - fault/shear zone. Then, moderately altered GND, lim on frac, more competent than above. Fractured @ 99.48m.						
10		96.68	100.58	Broken GND, Lim on frac						
10		100.58	101.58	Unaltered GND. Fragmented @ 101.46m. Vein @ 100.96m.						
10		101.58	102.11	GND fragmented until 100.68m, becomes fractured w/ lim on fracs						
10		102.11	102.73	Mod'ly alt'd GND. Pervasive lim	2	1		2		
10		102.73	103.63	Broken GND frags (max 6cm). Lim on frac.	1					
10		103.63	103.94	Mod alt GND. Reddish brown colour	3					
10		103.94	104.43	Less altered	1					
10		104.43	105.36	Intensely altered GND. Sugary texture, qtz eyes present w/ GND frags. Qtz veins fractured and offset	3	2		2		
10		105.36	110.51	Intensely altered GND. Core is yellow-beige w/ rusty patches. Qtz eyes, bt and GND frags present in clay. Veins are fractured or broken. Hydrothermal alt'n on shear zne. No obvious lineation or orientation indicators	2	2		3		
10		110.51	111.88	Slight to mod alt'n in GND. Core is fractured w/ pervasive lim as well as on fracs	2	2		1		
10		111.88	113.08	Core is fractured and broken. Qtz veins present, but broken	2	1		1		
10		113.08	114.44	Mod'ly alt'd GND. Sugary texture; becomes more altered to clay @114.12m	1	1		2		
10		114.44	115.52	Fractured GND. Lim on fracs	1					
10		115.52	115.82							
10		115.82	116.83	Mod'ly alt'd GND. Overall colour is med brown w/ alignments of yellow clay minerals (w/ sulphur?). Limonite, including siderite, on fracs	4	1		2	1	
10		116.83	117.90	Minor alt'n in GND. Veinlets noted here because they're different in appearance - straight w/ large selvages; Set of 2 veinlets @117.45 to 117.50m	1	1			1	
10		117.90	119.06	Minor alt'n in GND. Qtz/carb veins have large selvages. Shear sense indicator (drawn), sinistral movement.	1	1	1		3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
1	1	3.00	3.0							2.0	1.0							5.0				B291522	67.06	68.58	**0.087**	DUP		VA05044876	1.52
1	1	1.50	1.5	35	145	0.2	lim	3	4		0.1		0.1									B291523	68.58	70.10	**0.118**			VA05044876	1.52
1	1	0.50	0.5	70		0.2	lim/q	3	4	0.0								0.0				B291524	70.10	71.63	**0.153**			VA05044876	1.53
3	1	1.00	3.0	45		1.0	q	3	1	2.0			5.0					5.0				B291525	71.63	73.15	**0.599**		aspy in margins, py in vein	VA05044876	1.52
1	1	3.00	3.0	50																		B291526	73.15	74.50	**0.251**			VA05044876	1.35
																						B291527	74.50	75.71	**0.199**			VA05044876	1.21
																						B291528	75.71	76.20	**0.066**			VA05044876	0.49
																						B291529	75.71	76.20	**0.124**	PD/CA		VA05044876	0.49
																						B291530	STANDARD 3C		**0.844**	3C		VA05044876	
3	1	1.00	3.0	45						0.1			1.0									B291531	76.20	77.72	**0.297**			VA05044876	1.52
1	6	0.20	0.2	30	0					25.0			5.0					4.5				B291532	77.72	79.25	**0.434**			VA05044876	1.53
3	1	1.30	3.3	35						10.0			2.0					5.0											
2	1	5.00	5.5	50	60	0.0							1.0									B291533	79.25	80.77	**0.326**			VA05044876	1.52
1	3	4.00	4.0	40		0.0																B291534	80.77	81.52	**0.349**			VA05044876	0.75
0																						B291535	81.52	82.55	**0.094**			VA05044876	1.03
																						B291536	BLANK		**<0.005**			VA05044876	
0																						B291537	82.55	83.82	**0.070**			VA05044876	1.27
3	1	1.00	2.0	60									1.0					5.0				B291538	83.82	85.34	**0.276**			VA05044876	1.52
1																						B291539	85.34	86.87	**0.051**		broken and fragmented	VA05044876	1.53
1	1	1.00	1.0	45		1.0	chl/q	4	1				1.0									B291540	86.87	87.40	**0.127**			VA05044876	0.53
2	1	2.00	4.0							3.0			1.0					2.0				B291541	87.40	87.77	**0.060**			VA05044876	0.37
2	1	2.00	4.0							3.0			1.0					2.0				B291542	87.40	87.77	**0.153**	DUP		VA05044876	0.37
5	1	3.00	4.5	50		1.0	q	3	1		5.0	3.0	3.0					3.0				B291543	87.77	88.24	**1.965**			VA05044876	0.47
2	1	1.00	2.0	70									2.0									B291544	88.24	88.92	**0.177**			VA05044876	0.68
5	1	1.00	3.5	60		2.0	chl	3	1				3.0					1.0				B291545	88.92	91.44	**0.150**			VA05044876	2.52
2	1																					B291546	91.44	92.96	**0.082**		Veins are broken and fractured, unable to get orientation information	VA05044876	1.52
																						B291547	92.96	94.49	**0.146**			VA05044876	1.53
1	1					6.0							1.0									B291548	94.49	96.01	**0.042**		qtz veins present, but orientation unrecognizable due to shear	VA05044876	1.52
1	1					6.0							1.0									B291549	94.49	96.01	**0.048**	PD/CA		VA05044876	1.52
																						B291550	STANDARD 5E		**1.475**	5E		VA05044876	
																						B291551	96.01	97.54	**0.110**			VA05044876	1.53
2	1	3.00	4.0	45		0.0							0.1									B291552	97.54	99.06	**0.183**			VA05044876	1.52
1	1	1.00	1.0	50		0.0							1.0									B291553	99.06	99.68	**0.351**			VA05044876	0.62
2	1	1.00	2.0	50		0.5	q	3	1				2.0					4.0				B291554	99.68	101.58	**0.035**			VA05044876	1.90
2	1	0.30	0.6	50		0.1	q	2	2		3.0		5.0					4.0				B291555	101.58	102.73	**0.300**			VA05044876	1.15
																						B291556	BLANK		**<0.005**			VA05044876	
1	1	0.30	0.3	35									1.0					5.0				B291557	102.73	103.63	**0.085**			VA05044876	0.90
4	1	1.50	2.1	45								1.0						5.0				B291558	103.63	104.43	**0.049**			VA05044876	0.80
1	1	1.00	1.0	55		1.0			3	2.0								4.0				B291559	104.43	105.36	**0.339**			VA05044876	0.93
																						B291560	105.36	106.68	**0.055**			VA05044876	1.32
																						B291561	106.68	108.20	**0.121**			VA05044876	1.52
																						B291562	106.68	108.20	**0.044**	DUP		VA05044876	1.52
																						B291563	108.20	109.73	**0.092**			VA05044876	1.53
																						B291564	109.73	110.51	**0.039**			VA05044876	0.78
4	1	2.00	4.0	40									3.0					5.0				B291565	110.51	111.88	**0.099**			VA05044876	1.37
1	1												1.0					4.0				B291566	111.88	113.08	**0.084**			VA05044876	1.20
1	1																					B291567	113.08	114.44	**0.308**			VA05044876	1.36
1	1																					B291568	114.44	115.85	**0.017**			VA05044876	1.41
1	1																					B291569	114.44	115.85	**0.018**	PD/CA		VA05044876	1.41
																						B291570	STANDARD 3C		**0.091**	3C		VA05044876	
1	1	0.50	0.5	25		2.0	q/s	3	4	0.0								0.0				B291571	115.82	116.83	**0.061**		first vein straight second branching	VA05044876	1.01
1	1	5.00	5.0	30		1.0	q/s	2	3	5.0			2.0					5.0	1.0										
3	1	2.50	5.0	25	40	3.0	q/s	3	2	3.0			1.0					4.0	3.0			B291572	116.83	117.90	**0.077**			VA05044876	1.07
2	1	0.20	0.4	35		2.0	q	3	1				2.0																
4	3	1.00	2.0	50	30	17.0	q/s/chl	4	1	15.0			0.1					5.0				B291573	117.90	119.06	**0.020**			VA05044876	1.16

DRILL LOG LEGEND P1	DATE: June 1 - 4, 2005 PAGE 5 of 8		
DRILL HOLE # : DG05-278C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		119.06	120.24	Unaltered GND where selvage from large qtz veins not affecting	1	1	1		1	
10		120.24	120.67	Mod'ly alt'd GND	1	2	1	1		
10		120.67	122.09	Unaltered GND. Lim on fracs	1	1				
10		122.09	123.63	Unaltered GND. Lim on fracs; sericite weathered to clay minerals on fracs	1	1		1		
10		123.63	124.97	Minor to unaltered GND. Po. Is pale bronzy silver coloured. Highly altered section (ser=1, chl=3, carb=3), from 123.80 to 124.00m.	1	2			1	
10		124.97	126.49	Unaltered section of GND w/ 7 congruent qtz veins. Aspy/scor concentrated at margins of straight, narrow veins. Some calcite along veins as well (~10%). 5cm x 3cm bleb of alt'd GND, to dark grey. Bt crystals still visible, few small (2mm) qtz crystals as well. Weakly magnetic; Hematite/magnetite(?) @125.18m.					1	
10		126.49	128.02	Unaltered GND except selvages					1	
10		128.02	128.68	GND dominated by silicified selvages of qtz veins. ~10cm gaps between selvages are unaltered. Selvage contains lots of dissem aspy and po.						
10		128.68	128.97	Silicified zone abuts unaltered GND @ 10° to CA. Diss aspy/scor and po. If qtz vein *was* here, it's not visible (possibly just outside core range).						
10		128.97	130.55	Unaltered GND. Qtz veins begin at 129.92m.						
10		130.55	131.44	Unaltered GND. Narrow silicified vein branches w/ scorodite/aspy and minor py. Minor lim on fractures.						
10		131.44	132.36	Unaltered GND						
		132.26	133.10							
10		133.10	133.85	Chlorite alteration zone. Core is bleached to white and green "speckled" core w/ a 3cm qtz vein @35-40° to CA. V. tr aspy disseminated w/in vein material. Mafics are completely depleted		3	3			
10		133.85	142.95							
10		142.95	144.49	Core is altered to a limonite/rusty brown; core is soft yet coherent, sericite and limonite are pervasive. Some clay ~1 3%	2	1		1		
10		144.49	148.38	White, soft carbonates are fracture filling into competent GND. Essentially x-cutting/carbonate stringer veinlets					1	
10		148.38	149.35	GND is fractured / healed w/ carbonate veinlets. Veinlets are gouge - soft and pure flour white.					1	
10		149.35	152.40							
10		152.40	154.40	GND as previous unit (148.38-149.35m), except that some carbonate vns are thicker (~0.25cm) and are running parallel to C.A. No visible sulphides disseminated within the calcite / carbonate vns/vnlets.					1	
10		154.40	158.50							
10		158.50	160.02	GND is oxidized slightly w/ pervasive limonite, minor sericite (both as fracture filling and somewhat pervasive). Core is rusty yellow/brown yet competent.	2	1			1	
10		160.02	163.70	Sheeted vn system appears. Vns are regular and similar. Vns are ave. 0.5-3.75cm in width. They have regular spacings of ~ 5-15cm apart @ an ave angles of 35-40°. Predominant noted sulphide is pyrrhotite @ tr-2%, as disseminations within the vns.		1	1			
10		163.70	164.59							
10		164.59	165.60	Mod'ly alt'd GND. Overall colour is pale whitish green with uneven patches, up to 10cm long of less altered GND, which is pale grey. One straight fracture face (25° to CA) is covered with powdery black alt'n product with various diss. sulphides (aspy, cpy and chalcocite (?) - striated dull gold colour + black granular aggregates), 0.5cm wide, at 165.18m.		3	3	1		
10		165.60	166.86	Unaltered except for wide selvages around qtz veins at beginning of sample. At least minor sericite throughout entire sample.		2	2		1	
10		166.86	167.14	14cm qtz vein: translucent milky white. Selvage also included in sample (total: 28cm).						
10		167.14	168.22	Alt'n is minor but rock is very broken up; fractures near parallel to CA and at ~80° to CA.		2	1		1	
10		168.22	169.43	Minor to mod alt'n in GND. Near-parallel fractures still prevalent but rock is more competent (less high-angle fractures).		3	2		1	
10		169.43	170.96	Minor to mod alt'n in GND. Massive sulphides (vein) beside qtz vein at 170.75m - noted on sample ticket. Minor diss sulphides throughout section (aspy, po).		3	3			
10		170.96	172.56	Extreme alt'n here. Whole sample is gouged out clay material with ~40% remnant GND material: qtz eyes, hb crystals (~2mm), etc.	2	2		4	2	
10		172.56	173.74	Mod'ly alt'd GND. Colinear fractures at 50° to CA (?).		3	1	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	4.00	6.0	20	30	15.0	q/s/chl	4	5		8.0							3.0				B291574	119.06	120.24	0.077			VA05044876	1.18
1	1	0.40	0.4	50		2.0	q/s/chl	2			2.0											B291575	120.24	120.67	0.640			VA05044876	0.43
																						B291576	BLANK		<0.005			VA05044876	
2	1	0.30	0.6	35		1.0	q/s	3			3.0											B291577	120.67	122.09	0.032			VA05044876	1.42
5	1	1.20	3.6	30	40	1.0	q/s	2			10.0											B291578	122.09	123.63	0.095			VA05044876	1.54
5	1	1.30	5.0	45		0.5	q/s	2		2.0	3.0							5.0				B291579	123.63	124.97	0.018			VA05044876	1.34
7	1	1.50	5.5	30	40	1.0	q/s/cb	3			10.0		5.0					2.0	5.0			B291580	124.97	126.49	0.164			VA05044876	1.52
2	1	0.80	1.4	10		1.0	q	3			0.1		5.0									B291581	126.49	128.02	0.341			VA05044876	1.53
11	1	1.30	4.0	40	50	1.0	q/chl	3			10.0	0.1	5.0						3.0									VA05044876	
11	1	1.30	4.0	40	50	1.0	q/chl	3			10.0	0.1	5.0						3.0			B291582	126.49	128.02	0.087	DUP	1 vein @50°	VA05044876	1.53
5	1	0.70	2.5	20	30	10.0	q	4			10.0	1.0	15.0							1.0		B291583	128.02	128.68	0.319		1 vein @30°	VA05044876	0.66
											20.0		20.0						3.0			B291584	128.68	128.97	0.029			VA05044876	0.29
6	1	0.50	2.4	30	40	1.0	q	3		5.0			10.0						3.0			B291585	128.97	130.55	0.024			VA05044876	1.58
										10.0			10.0						4.0			B291586	130.55	131.44	0.032			VA05044876	0.89
3	1	0.30	0.9	25	45	1.0	q	3		20.0			5.0					4.0	2.0			B291587	131.44	132.36	0.050			VA05044876	0.92
6	1	1.25	6.0	20	45						5.0											B291588	132.36	132.82	0.239			VA05044876	0.46
6	1	1.25	6.0	20	45						5.0											B291589	132.36	132.82	0.136	PD/CA		VA05044876	0.46
																						B291590	STANDARD 2B		3.260	2B		VA05044876	
4	1	3.00	3.75	30	40						0.1		0.1									B291591	132.82	133.85	0.153			VA05044876	1.03
4	1	1.00	2.0	30	35						0.1		0.1									B291592	133.85	135.64	0.020			VA05044876	1.79
4	1	1.00	2.5	40							0.1		0.1									B291593	135.64	137.16	0.349			VA05044876	1.52
2	1	1.50	2.0	30	35						0.1		1.0									B291594	137.16	138.68	0.045			VA05044876	1.52
2	1	1.00	2.0	40							0.1		0.1									B291595	138.68	140.21	0.210			VA05044876	1.53
																						B291596	BLANK		<0.005			VA05044876	
7	1	0.75	2.5	40	30						0.1											B291597	140.21	141.73	0.027			VA05044876	1.52
																						B291598	141.73	142.95	0.012			VA05044876	1.22
																						B291599	142.95	144.49	0.023			VA05044876	1.54
3	1	0.50	1.0	40		0.1					0.1											B291600	144.49	146.30	0.014		sericite on selvages	VA05044876	1.81
2	1	0.75	1.5	30							0.1											B291601	146.30	147.83	0.009			VA05044876	1.53
2	1	0.75	1.5	30							0.1											B291602	146.30	147.83	1.910	DUP		VA05044876	1.53
						0.1		1														B291603	147.83	148.38	0.041			VA05044876	0.55
																						B291604	148.38	149.35	0.018			VA05044876	0.97
4	1	1.00	2.0	40	50						0.1		0.1									B291605	149.35	150.88	0.285			VA05044876	1.53
4	1	0.75	2.5	30							0.1											B291606	150.88	152.40	0.165			VA05044876	1.52
8	1	1.00	8.0	30	35						1.0		0.1									B291607	152.40	153.92	0.068			VA05044876	1.52
4	1	2.50	4.0	25	40						0.1											B291608	153.92	155.45	0.015			VA05044876	1.53
4	1	2.50	4.0	25	40						0.1											B291609	153.92	155.45	0.012	PD/CA		VA05044876	1.53
																						B291610	STANDARD 5E		1.35	5E		VA05046431	
4	1	3.00	3.75	25	45	0.1		1			0.1											B291611	155.45	156.97	0.047			VA05046431	1.52
4	1	0.50	1.0	15	40						0.1		0.1									B291612	156.97	158.50	0.04			VA05046431	1.53
						0.1		1					0.1									B291613	158.50	160.02	0.046			VA05046431	1.52
1	1	3.00	3.0	35							0.1											B291614	160.02	161.26	0.01			VA05046431	1.24
10	1	3.75	22.5	35	40						2.0											B291615	161.26	163.07	0.31			VA05046431	1.81
																						B291616	BLANK		<0.005			VA05046431	
6	1	1.25	3.5	35	40						1.0											B291617	163.07	164.59	0.159			VA05046431	1.52
1	6	0.50	0.5	30					0	5.0		20.0	2.0					3.0				B291618	164.59	165.60	0.077		selvage all altered - cannot distinguish	VA05046431	1.01
2	1	1.20	1.8	40	135					10.0			2.0																
3	1	1.00	2.5	35	50	8.0	chl/s/q	5		8.0	10.0	5.0	0.1									B291619	165.60	166.86	0.06			VA05046431	1.26
1	1	14.00	14.0	45		14.0	chl/s/cb	4	0	5.0	4.0	0.1						2.0				B291620	166.86	167.14	0.45		no alteration of 'rock' b/c sample is qtz vein w/selvage	VA05046431	0.28
2	1	0.60	1.0	45	25	1.5	chl/s	4	0		10.0		0.1									B291621	167.14	168.22	0.015			VA05046431	1.08
2	1	0.60	1.0	45	25	1.5	chl/s	4	0		10.0		0.1									B291622	167.14	168.22	0.011	DUP		VA05046431	1.08
1	1	1.50	1.5	30		1.0	chl/s	3		3.0								3.0				B291623	168.22	170.96	0.049			VA05046431	2.74
1	3	0.40	0.4	40	20	20.0	chl/s/cb	5		0.1																			
1	1	1.00	1.0	55		2.0	chl/s/q	4	0		15.0																margins abrupt		
1	1	1.50	1.5	25		4.0	chl/s/q	4			0.1		1.0														margins silicified		
2	6	1.00	2.0	25	30	10.0	chl	5			1.0		5.0				15										chalcocite?		
0																						B291624	170.96	172.56	0.025		no veins visible	VA05046431	1.60
3	1	1.50	3.5	150	40	0.5	chl/s	2	0		0.1		0.1									B291625	172.56	173.74	0.019			VA05046431	1.18
1	1	0.80	0.8	50		1.0	chl/s	1	0	0.0												B291626	173.74	175.26	0.043			VA05046431	1.52

DRILL LOG LEGEND P1	DATE: June 1 - 4, 2005 PAGE 7 of 8		
DRILL HOLE # : DG05-278C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		173.74	175.26	Highly alt'd GND. 30-60% weathered out to clay minerals. Matrix material totally alt'd, so only large qtz and mafics left of GND. Clay vein at 20° to CA shows slickensides at ~80° to CA. Fractures at 50° continue; fract faces have		3	2	2	1	
10		175.26	176.78	Highly alt'd GND. 60% gone to clay minerals and sericite. One fracture face (to 15°) is light grey clay.	1	3	2	2	1	
10		176.78	178.31	Uneven fracture set at ~90° to CA. Highly alt'd GND cont'd. Qtz vein offset approx. 3cm, sinistral. (figures on original log sheet)	1	3	3	2	1	
10		178.31	179.83	Gradation over 30cm to very minor alt'n in the GND. First 30cm more silicified w/ grey qtz. One massive sulphide veinlet at 178.92m. Microfractures, randomly oriented, are infilled with calcite.		3		1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 1 - 4, 2005

LOGGED BY: T. Croteau/M. Stone/ K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL											Sample Number	Interval		Au (g/T)	Sample Type	Vein Comments	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	3.00	4.0	65			chl/s/q	3	1	0.0												B291627	175.26	176.78	**0.062**		selvage gone to alt'n	VA05046431	1.52
1	1	3.00	3.0	85		8.0	chl/s	3	1		2.0		1.0						3.0			B291628	176.78	178.31	**0.031**			VA05046431	1.53
1	1	3.00	3.0	85		8.0	chl/s	3	1		2.0		1.0						3.0			B291629	176.78	178.31	**0.03**	PD/CA		VA05046431	1.53
																						B291630	STANDARD 7G		**4.34**	7G		VA05046431	
1	6	0.30	0.3	35		1.5	q/chl	4		10.0	20.0							5.0				B291631	178.31	179.83	**0.024**			VA05046431	1.52
																								E.O.H.				

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-279C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1024m

BEARING: 000 | **DIP: -50°**

DATE STARTED: June 4, 2005 (night) | **DATE COMPLETED:** June 8, 2005 (day)

COORD SYSTEM: NAD 27: **EASTING: 459701 NORTHING: 7099261**

COORD SYSTEM: NAD 83: **EASTING: 459586 NORTHING: 7099443**

NAD 27 (CORRECTED for historic grid): **EASTING: 459671 NORTHING: 7099271**

LOGGED BY:
Melodie Stone, Terry Croteau, Kristian Whitehead

SECTION LINE (historic grid): 459671E

CONTRACTOR:
Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 9.14
Deviation:
Casing: 9.14m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B291632 to B291823
Requisition #: MASP448STRGOL.05Q — Date Shipped: 10-June-05
Lab Record #: VA05046971 — Date Received: 16-June-05

Duplicates:	B291642, B291662, B291682, B291702, B291722, B291742, B291762, B291782, B291802, B291822
Preparation Duplicate/ Check Assay:	B291649, B291669, B291689, B291709, B291729, B291749, B291769, B291789, B291809
Standards:	B291650(4D), B291670(1A), B291690(4D), B291710(7G), B291730(1A), B291750(4D), B291770(3C), B291790(4D), B291810(2B)
Blanks:	B291656, B291676, B291696, B291716, B291736, B291756, B291776, B291796, B291816

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+ 27 Corr)
50	335	49	001	002
100	334.3	49.2	000.3	001.3
200	334.8	48.4	000.8	001.8

LITHOLOGY

FROM	TO	
9.14m	201.17m	GND

ALTERATION

FROM	TO	
15	35	ox, ser, chl, arg, carb
55	65	ox, ser, chl, arg, carb
95	112	ox, ser, chl, arg, carb
135	175	ox, ser, chl, arg, carb
185	190	ox, ser, chl, arg, carb

MINERALIZATION (Veins)

FROM	TO	
10	30	py, aspy, minor po
94	125	py, po, asy, v.minor cpy
134	160	py, po, aspy
168	201	py, aspy, po, v.minor cpy

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005 PAGE	of 12							
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence						
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41									
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MBED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93									

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-9.14m			CASING (no recovery)						
10	9.14-201.17	9.14	15.24	V. broken and heavily oxidized GND. Alteration from minor to moderate. Veinlets grey qtz. V. poor recovery from 12.19 to 13.72m (19%). Rock is pebble-cobble size.	4	2				
10		15.24	18.29	Mod. to highly alt'd GND. One qtz vein has bands of alternating siderite and qtz. Adjacent to this is a zone of dark grey-black, grainy alt'n (old xeno?), ~6x4cm.	4	1			1	
10		18.29	24.38	Mod to highly alt'd GND. V. broken core: max 10cm long (1), most <5cm. From 21.34 to 24.38m recovery is poor (34% and 16%). Fewer small pebbles but core is still v. broken.	4	1			1	
10		24.38	25.91	V. broken core w/ one 20cm gouge zone, med. brown.	4	1		2		
10		25.91	27.43	Highly alt'd and broken core - one 10cm length. Colour pale brown.	4	2	1	1		
10		27.43	28.96	Highly to extremely alt'd GND.	4	2	1	1		
10		28.96	30.46	13% core recovery. Gouge to highly alt'd GND.	4	1		3		
10		30.46	32.00	Extremely alt'd to clay texture (90%), with qtz eyes and small GND pebbles	4	2		4	1	
10		32.00	33.56	Poor core recovery (14%). Pebbles.	4	1		2		
10		33.56	34.90	Extremely alt'd GND. Sand-sized, medium brown.	4			3	1	
10		34.90	36.40	Highly alt'd GND. Cobbles no bigger than 5cm. Veinlet at 34.05m w/ 1cm selvage (ox. 100%)	4	1		1	1	
10		36.40	39.37	Highly alt'd GND. Hematite oxidized near qtz veins (2mm subhedral grains).	4	1	1	2	1	
10		39.37	40.50	Highly alt'd GND. More competent, however, with pieces up to 15cm. Black ox'n product on uneven fracture faces. Limonite on microfractures. Gouge zone (5cm) between 2 competent, 6cm GND pieces. No slickensides.	5	2	1	1	1	
10		40.50	42.67	Extremely alt'd GND. Clay to sand-size (90%). Medium brown.	4	2	1	3	2	
10		42.67	43.76							
10		43.76	46.80	GND is v. broken and altered to gouge/sandy gravel with v. minor competent pieces. Core is v. limonite stained on fracs / pervasively and within clay yielding a rusty/yellow-brown color. Sulphides have undergone significant weathering (po + aspy). Qtz pieces in the core are visible indicating vning however thickness / amount and angle to CA are impossible to obtain. Sulphides are within veining or immediately adjacent.	4	2		2		
10		46.80	47.57							
10		47.57	48.90	GND becomes sandy, predominantly, w/ pieces of gravel and clay. Core is heavy limonite-stained and fracs are occasionally hematite-stained as thin skin on surface (black).	2	1		1		
10		48.90	49.03	Fault gouge with heavy limonite staining. Qtz vns w/ slickensides indicating fault movement, angle on surface is ~ 50° to CA.	3	1		2		
10		49.03	49.15							
10		49.15	50.01	At 49.15m is a 0.25cm wide oxidized pyrite vn, pure black, @~ 50° to CA.	5					
10		50.01	50.29	Fault gouge with a slickenside surface on contact at 35° to CA.	2	2		3		
10		50.29	50.41							
10		50.41	53.34	Core is altered to crumbly gouge w/ pervasive limonite and sericite. Core is v. soft yet recovery is good. Some vning can be seen but highly oxidized pyrite is interpretation.	2	4		2	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	0.5	1.0	25		2.0	q	3	2	5.0			5.0					5.0				B291632	9.14	10.67	0.297			VA05046971	1.53
1	1.0	3.0	40	10	0.5	q	3	2	5.0			5.0					5.0				B291633	10.67	12.19	0.175			VA05046971	1.52
																					B291634	12.19	13.72	0.227			VA05046971	1.53
1	1.0	2.5			1.0	q/s	3	3	0.1								5.0				B291635	13.80	15.24	0.083		pebbles of qtz (no angle avail.)	VA05046971	1.44
																					B291636	BLANK		<0.005			VA05046971	
1	3.0	5.0	50		1.0	q/cb	5	3	5.0			0.1					5.0				B291637	15.24	16.76	0.471			VA05046971	1.52
1	1.0	2.5	50		1.0	q	3	3	7.0			3.0					5.0	3.0			B291638	16.76	18.29	5.250		qtz on broken pieces	VA05046971	1.53
1	1.3	5.0	30		3.0	q/s	3	4	0.1			2.0					0.0	0.0			B291639	18.29	19.81	0.364			VA05046971	1.52
1	2.0	4.0	60					4				2.0					.	1.0			B291640	19.81	21.34	0.280		whole sample is altered - no selvage info	VA05046971	1.53
1	1.5	3.5	30		2.0	q	4	3	1.0			1.0						2.0			B291641	21.34	22.86	0.780			VA05046971	1.52
1	1.5	3.5	30		2.0	q	4	3	1.0			1.0						2.0			B291642	21.34	22.86	0.432	DUP		VA05046971	1.52
																					B291643	22.86	24.38	0.149			VA05046971	1.52
1	1.2	4.0	50		6.0	q	4	3	2.0			2.0					5.0				B291644	24.38	25.91	1.290			VA05046971	1.53
1	1.5	4.0	55	25	2.0	q/s	1	4				2.0									B291645	25.91	27.43	0.969			VA05046971	1.52
1	1.0	2.0	60	95	2.0	q	4	4	3.0			3.0					4.0				B291646	27.43	28.96	0.440			VA05046971	1.53
																					B291647	28.96	30.48	0.301			VA05046971	1.52
1	1.0	1.0	85																		B291648	30.48	32.00	1.030		whole sample is altered - no selvage info	VA05046971	1.52
1	1.0	1.0	85																		B291649	30.48	32.00	1.215	PD/CA		VA05046971	1.52
																					B291650	STANDARD 4D		0.416	4D		VA05046971	
1	1.0	1.0																			B291651	32.00	33.53	2.510		pebbles of qtz (no angle avail.), selvage altered	VA05046971	1.53
																					B291652	33.53	34.90	0.880			VA05046971	1.37
2	1.0	1.0	90														4.0				B291653	34.90	36.40	1.045		whole sample is altered - no selvage info	VA05046971	1.50
																					B291654	36.40	37.90	0.124			VA05046971	1.50
1	1.5	3.0	10		1.0	q	3	3	0.1								4.0				B291655	37.90	39.37	0.748			VA05046971	1.47
																					B291656	BLANK		<0.005			VA05046971	
1	0.5	0.5	65						0.1								4.0				B291657	39.37	40.50	0.109		qtz vein on small piece, not intersecting CA	VA05046971	1.13
1	0.5	0.5										0.1						4.0			B291658	40.50	41.20	0.325		can't see selvage	VA05046971	0.70
1	0.5	1.0							3.0			4.0					4.0	4.0			B291659	41.20	42.67	2.210		milky qtz on pebbles	VA05046971	1.47
1	0.5	2.0	50		0.1		2	2	0.1								4.0				B291660	42.67	44.20	0.383		2 qtz veins & qtz pieces	VA05046971	1.53
1	0.5	1.0	55	60																	B291661	44.20	45.72	0.359		2 qtz veins & qtz pieces	VA05046971	1.52
1	0.5	1.0	55	60																	B291662	44.20	45.72	0.263	DUP		VA05046971	1.52
1					0.1		1	1	0.1			0.1					4.0				B291663	45.72	47.24	0.618		1 qtz vein & qtz pieces	VA05046971	1.52
1			45	50					0.1			0.1									B291664	47.24	48.77	0.768		2 qtz veins & qtz pieces	VA05046971	1.53
1	1.25	3.0							0.1			1.0					4.0				B291665	48.77	50.29	0.499		KW noted up to 80% py in some veins	VA05046971	1.52
																					B291666	50.29	51.82	0.367			VA05046971	1.53
																					B291667	51.82	53.34	0.470			VA05046971	1.52

DRILL LOG LEGEND P1			DATE: June 4 - 8, 2005 PAGE 3 of 12								
DRILL HOLE # : DG05-279C			FeOx 0 = Unoxidized 5 = Intensely Ox'd		Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered				Carbonate 0 = No Effervescence 5 = Strong Effervescence		
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93											
UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
10		53.34	54.86	Chloritized GND core, bleached, green-hued w/ little to no mafics. Minor calcite stringers (frac-filling mostly). Limonite on fracs, looks to be oxidized py on fracs.	2	2	2		1		
10		54.86	55.44								
10		55.44	55.84	Clay gouge alteration zone. Qtz eyes, looks like digested, rotten GND. Limonite abundant, making core / clay yellow-gold color.	2	1		4			
10		55.84	59.31								
10		59.31	59.91	Hydrothermal alteration zone, core becomes sandy to clay w/ some broken pieces. Heavy limonite staining. Qtz eyes present. Some red rusty bits (perhaps weathered sulphides).	3	1		2			
10		59.91	60.96	GND, same as previous unit	3	1		3	2		
10		60.96	64.01	Core has what looks to be a sheeted vn system. Veins are spaced ~ 5-10cm apart w/ similar core axis foliation of 45-50°. Minor dissem sulphides in vns.							
10		64.01	64.66	GND becomes etched and filled w/ limonite and sericite. Some bleaching through mafics. Intact core is easily broken w/ v. minor clay seems. Core is yellow-gold stained in color	3	2		1			
10		64.66	65.13	Large qtz vn. Some limonite and GND inclusive					1		
		65.13	66.78								
10		66.78	67.06	Gouge clay alteration seam, core reduced to sandy clay w/ small qtz eyes, heavy limonite staining. Qtz pieces indicating vning but too small to be certain.	2	1		4	1		
10		67.06	67.40								
10		67.40	67.78	Same GND as above, but w/ no qtz veining visible	2	1		4			
10		67.78	68.17								
10		68.17	69.15	GND becomes altered to bleached, sericite, grey-brown dull color. Minor green (chlorite hue) but not intense. Pervasive limonite, yet core is coherent. Abundant selvages w/ minor sulphides (aspy). Very little to no mafics, qtz vns visible @45-50° to CA, ~0.25-0.5cm thick, and continues to 96.68m.	3	1	2				
10		69.15	70.10								
10		70.10	72.23	Core is extremely broken to gravel and clay. Clay seams have reddish colours, possibly indicating py oxidation. Core is yellow-gold/rusty colour. Core has lost mafics in places, and has slight bleached/chloritic nature. Evidence of hydrothermal/faulting.	4	1	1	1			
10		72.23	75.38	GND is altered to a predominantly mafic-'free' state w/ only minor units of visible mafics. Core has a dull brown colour with visible sericite and minor chlorite. Some siderite w/in selvages. @74.34m pyrite vein oxidized to red/black and minor unoxidized crystals. Vein is ~0.75-1.5cm thick, at 50° to CA.	3	1	1				
10		75.38	76.02	Altered clay seam, hydrothermal alteration is evident from visible qtz eyes and some preserved gravel sized pieces of altered GND. Clay is yellow/gold and consistent in texture. No contacts preserved.	3			4			
10		76.02	77.50	Core remains altered as described in previous section (72.23-75.38m)	3	1	1.0				
10		77.50	83.82	Core remains altered as above description w/ what appears as a sheeted vein system. Veining/selvages are somewhat regular w/ spacing @5-20cm apart w/ a regular angle of 45-50° to CA.	2	1	1				
10		83.82	84.08	Clay seam at hydro alteration zone w/ a 5cm adjacent sulphide (aspy stringer) and veining zone. @84.08-84.13m, clay is gold yellow colour w/ qtz eyes	2	1		4			
10		84.08	89.37	Same as above unit, altered GND. description from 72.23-75.38m interval.	3	1	1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
					Selvages				Sulphides									Oxidation											
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
1	0.25	0.25	55	60					0.1			0.1					4.0				B291668	53.34	54.86	**0.356**			VA05046971	1.52
1	0.25	0.25	55	60					0.1			0.1					4.0				B291669	53.34	54.86	**0.406**	PD/CA		VA05046971	1.52
																					B291670	ANDARD 1A		**0.754**	1A		VA05046971	
1	0.75	2.0	45	50					0.1								5.0				B291671	54.86	56.39	**0.135**			VA05046971	1.53
1	1.0	1.0							0.1								5.0				B291672	56.39	57.91	**0.156**		1 qtz vein & qtz pieces	VA05046971	1.52
1	0.25	2.75	15	45								0.1					1.0				B291673	57.91	59.44	**0.191**			VA05046971	1.53
1	2.25	3.0	55		0.1		2		0.1								4.0				B291674	59.44	60.96	**2.300**		2 veins plus pieces	VA05046971	1.52
1	1.0	3.0	45	50	0.1		1		0.1	0.1							2.0				B291675	60.96	62.48	**1.055**			VA05046971	1.52
																					B291676	BLANK		**<0.005**			VA05046971	
1	1.0	4.0	45	50	0.1		2					0.1					3.0				B291677	62.48	64.01	**2.280**			VA05046971	1.53
1	46.5	46.5	75		0.1		2					0.1					4.0				B291678	64.01	65.53	**0.279**			VA05046971	1.52
																					B291679	65.53	67.06	**0.071**		Qtz pieces	VA05046971	1.53
																					B291680	67.06	67.85	**0.103**		Qtz pieces	VA05046971	0.79
1	1.25	3.0	45		0.1		1		0.1			0.1									B291681	67.85	70.10	**0.261**			VA05046971	2.25
1	1.25	3.0	45		0.1		1		0.1			0.1									B291682	67.85	70.10	**0.071**	DUP		VA05046971	2.25
																					B291683	70.10	71.63	**0.250**			VA05046971	1.53
1	0.25	0.25	30		0.1		1	2									2.0				B291684	71.63	73.15	**0.177**			VA05046971	1.52
1	0.75	1.5	35	50	0.1			1	0.0								3.0				B291685	73.15	74.68	**0.138**			VA05046971	1.53
6	0.75	1.5	35	50	0.1			1	100.0								3.0									7' includes qtz AND sulph veins		
1	1.75	4.0	70	45	0.1		1	1													B291686	74.68	75.38	**0.804**			VA05046971	0.70
																					B291687	75.38	76.02	**0.168**			VA05046971	0.64
1	0.75	1.25	40	50	0.2		1	2	2.0												B291688	76.02	76.20	**0.323**			VA05046971	0.18
1	0.75	1.25	40	50	0.2		1	2	2.0												B291689	76.02	76.20	**0.315**	PD/CA		VA05046971	0.18
																					B291690	STANDARD 4D		**0.417**	4D		VA05046971	
1	1.25	4.25	60		0.1		1	2	1.0								2.0				B291691	76.20	77.72	**0.530**			VA05046971	1.52
	2.0	5.5	50	60					1.0								2.0				B291692	77.72	79.25	**0.424**		4 veins and other pieces	VA05046971	1.53
1	1.5	5.75	45		0.1		2		0.1								2.0				B291693	79.25	80.77	**0.378**			VA05046971	1.52
1	1.5	1.0	45	50					1.0			5.0					2.0				B291694	80.77	82.30	**1.235**		max sulph percents	VA05046971	1.53
1	1.5	5.0	50	45	0.1		1					1.0					2.0				B291695	82.30	83.82	**0.506**			VA05046971	1.52
																					B291696	BLANK		**<0.005**			VA05046971	
1	1.25	5.0	35	45					0.1			0.1					2.0				B291697	83.82	85.34	**0.510**			VA05046971	1.52

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005	PAGE 5 of 12		
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		89.37	89.92	Clay seam w/ abundant qtz vn pieces with disseminations of aspy (trace).	2	2	1	3		
10		89.92	90.17							
10		90.17	90.48	Yellow-gold gouge w/ qtz eyes. Clay is relatively uniform; some minor pieces of altered GND. No visible sulphides. Inconclusive contact at 90.48m is preserved, @30-35° to CA.	2	1		3		
10		90.48	90.72							
10		90.72	90.80	Same gouge GND - description above	2	1		3		
10		90.80	91.32							
10		91.32	91.40	Same gouge GND - description above	2	1		3		
10		91.40	92.67							
10		92.67	92.80	Core becomes v. altered with dissems / vnlets of py and aspy (~2-5%). Somewhat oxidized at the contact @ 92.80m @ 60° to CA.	3	1				
10		92.80	93.13	Yellow to reddish-gold clay seam w/ GND rubble + qtz eyes. At 90.07m, a 1cm thick qtz vn @50-55° to CA (trace dissem py). At 93.13m, contact angle is 35° to CA.	3	1		5		
10		93.13	93.38	Core is v. decomposed but not to clay as yet. Qtz eyes are visible, core is soft but original altered brown core is still easily transparent. 93.38m: contact @~35° to CA, with some slickensides observed on adjacent GND. At 93.41, 93.53, and ~93.70m, 1-3cm thick qtz vns with py and aspy. Special Note: 68.17 to 96.68m, GND is of the same altered type best described in section: 72.23-75.38m.	4	1		1		
10		93.38	94.80	Zone of high to extreme alt'n. One block competent core at 93.29 to 93.67m, with 2 qtz veins. Rest of sample is gouge/extremely alt'd to clay texture w/ alignment of sericite/chlorite @~90° to CA. Colour from bluish green to light yellowish brown. 3rd qtz vein has been folded w/in competent alt'n zone.	5	4	3	2		
10		94.80	95.75	Highly alt'd but competent core. V. broken. Colour med. brown.	4	2	1	1		
10		95.75	96.01	Strong slickensides along qtz vein margin. Tourmaline (?striated, v. hard, transparent to translucent, colourless to brownish black), + qtz + sericite: fault zone. Sample is one qtz vein; broken up.						
10		96.01	97.54	Strong to moderate alt'n. 2 large qtz veins in first 30cm. Fault gouge at 96.30m for ~10cm w/ 80% sericite, aligned. Qtz vein offset (brittle), on fracture @35° to CA. Slickensides aligned with long axis.	3	3	1	1	1	
10		97.54	98.52	Mod'ly alt'd GND. Limonite on microfractures is pervasive. Xeno at 98.8m: fine-grained diorite.	3	1			1	
10		98.54	99.06	Highly alt'd zone. Competent core w/ regular fractures to 50°. Med brown. Almost no GND texture left (just rounded qtz grains).	3		1			
10		99.06	100.58	Mod'ly alt'd GND with two vein sets. High angle offsets low angle.	2	1				
10		100.58	102.11	Mod'ly alt'd GND. Regular fracture set (6) to 45° and 135°. One has fault gouge material (clay) w/ slickensides. Also slickensides noted on low angle fractures.	3	1		1	1	
10		102.11	103.30	V. broken core. Fracture sets @45°/135° and low angle (0-15°). Gouge material in two low angle fractures. No slickens obvious but calcite smeared out.	3	2	1	1	1	
10		103.30	104.81	Minor to moderate alteration - slow gradation through sample, due to increasing number of veins and veinlets (selvages account for alteration)	3	1	2			
10		104.81	106.97	Mod'ly alt'd GND, w/ >2cm qtz veins @45°. Limonite on irregular fractures. At 105.86m, 2cm fault gouge-clay shows slickensides. Colour brownish grey.	3	1	1	2	1	
10		106.97	107.90	High to extreme alt'n. Limonite and calcite up to 1cm wide. Colour medium to pale yellowish brown. Boundary to less alt'd GND (grey, coarse texture) is at 30° to CA. Patches of orange rust (siderite?) speckle qtz vein and surrounding rock (20cm).	4	2	2	2	1	
10		107.90	109.33	Minor alt'n around veins and veinlets. Two noticeable xenoliths at 108.9m and 109.3m	1	1				
10		109.33	120.40	Minor alt'd GND w/ qtz veins. Regular breaking at 45° and 135°. Calcite on fract faces (<1mm thick). Diss aspy near fract w/in unalt'd GND. At 116.43m rock fract at 50° to CA (3) and some clay alt'n occurred (5cm wide).	1					

DRILL LOG LEGEND P2

Date: June 4 - 8, 2005

PAGE 6 of 12

LOGGED BY: M. Stone / K. Whitehead

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL													Interval						
					Selvages				Sulphides									Oxidation										
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	jscordite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)
6	1.25	5.0	35	45					0.1			0.1					2.0									5' includes qtz AND sulph veins		
1	0.5	0.5	20		0.1		1					0.1									B291698	85.34	86.87	**0.198**			VA05046971	1.53
1	0.75	1.25	20	30	0.1		1		0.1			0.1					2.0				B291699	86.87	88.39	**0.278**			VA05046971	1.52
																					B291700	88.39	89.37	**0.510**			VA05046971	0.98
												0.1									B291701	89.37	89.92	**0.447**		Qtz pieces w/ clay	VA05046971	0.55
												0.1									B291702	89.37	89.92	**0.915**	DUP		VA05046971	0.55
																					B291703	89.92	90.60	**0.110**		broken core	VA05046971	0.68
																					B291704	90.60	91.44	**0.117**		broken core	VA05046971	0.84
																					B291705	91.44	92.68	**0.098**			VA05046971	1.24
1	0.75	0.75	50						0.1			0.1									B291706	92.68	93.38	**2.970**			VA05046971	0.70
1	2.0	4.0	40	10				4	10.0			10.0					5.0	2.0			B291707	93.38	94.23	**2.750**		selvage alt'd out	VA05046971	0.85
																					B291708	94.23	94.80	**1.390**			VA05046971	0.57
																					B291709	94.23	94.80	**1.495**	PD/CA		VA05046971	0.57
																					B291710	STANDARD 7G		**4.430**	7G		VA05046971	
1	2.0	2.0	35					4	2.0								5.0				B291711	94.80	95.75	**0.564**		selvage alt'd out	VA05046971	0.95
1	20.0																				B291712	95.75	96.01	**9.690**		no angles b/c qtz is all broken up. selvage in alt. zone	VA05046971	0.26
1	3.0	7.0	45	35				4				0.1						2.0			B291713	96.01	97.54	**0.837**		selvage alt'd out	VA05046971	1.53
6	0.5	0.5	30		1.0	q/s	4	2	30.0			5.0					4.0	3.0			B291714	97.54	98.52	**0.587**			VA05046971	0.98
1	0.3	0.3	45		1.0	q	3	2				1.0																
																					B291715	98.52	99.06	**0.226**			VA05046971	0.54
																					B291716	BLANK		**<0.005**			VA05046971	
1	1.0	4.5	70		6.0	q	5	4	5.0			10.0					5.0	4.0			B291717	99.06	100.58	**0.857**			VA05046971	1.52
1	1.0	3.0	25	15	1.0	q			3.0			5.0					5.0	2.0										
1	1.0	1.0	45		0.0				0.1								5.0				B291718	100.58	102.11	**1.100**			VA05046971	1.53
1	0.4	0.8	30	45	1.5	q	2	3	5.0			10.0					5.0	1.0			B291719	102.11	103.30	**1.015**			VA05046971	1.19
1	2.0	7.5	30	45	2.0	q/s	4	1	5.0	5.0		10.0					3.0				B291720	103.30	104.80	**0.527**			VA05046971	1.50
1	3.0	3.0	45		5.0	qcwx	13	1	2.0			0.1					4.0				B291721	104.80	105.82	**1.325**			VA05046971	1.02
1	3.0	3.0	45		5.0	qcwx	13	1	2.0			0.1					4.0				B291722	104.80	105.82	**0.816**	DUP		VA05046971	1.02
1	3.0	4.5	45									0.1						1.0			B291723	105.82	106.48	**1.615**		selvage alt'd out	VA05046971	0.66
																					B291724	106.48	106.97	**0.387**			VA05046971	0.49
1	0.3	0.3	45									0.1						1.0			B291725	106.97	107.90	**0.321**		selvage alt'd out	VA05046971	0.93
1	2.0	7.0	45	30	1.0	q/s	3	3	3.0			5.0					2.0	1.0			B291726	107.90	109.33	**1.425**			VA05046971	1.43
1	4.0	9.0	45		1.0	chl/q	3	2		10.0		8.0									B291727	109.33	110.29	**2.920**			VA05046971	0.96

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005	PAGE 7 of 12		
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chi, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		120.40	121.92	V. minor alt'n where qtz veins have dissipated into silicified zones (no clear vein boundaries) at 45° to CA w/ sulphides - included in the vein count, page 2.		1	1			
10		121.92	124.81	Qtz/aspy vein @ 45° to CA; 0.5cm. Aspy ~5-8%. GND adjacent on either side is bleached for ~3cm on either contact removing almost all mafics.	1					
10		124.81	130.03	AT 124.81m, a qtz/carb/sulphide aspy vein, @ 45-50°; width ranges from 0.5-0.75cm. Aspy is ~5% of vein components. No bleaching/alteration adjacent to vein	1	1			2	
10		130.03	130.50	Two 1cm qtz veins w/ 5cm chloritized margins.	2	1	2			
10		130.50	131.20	Chloritized/altered GND. Pervasively intruded w/ carbonate/qtz veining and sulphides (including ~1-10% py and ~5-15% aspy). Mafics are scarce in core. Core has a predominant grey colour. Zone ends w/ a slickensided surface @ 131.02m, 40° to CA.	2	1	1		2	
10		131.20	134.11							
10		134.11	135.64	GND altered throughout with calcite to crumbly texture. Approximately half the qtz veins are heavily silicified such that original vein is no longer seen as such, but more of a linear qtz-rich zone at the same angle as the real veins	1	1	1	1	3	
10		135.64	136.70	Minor alt'd. GND w/ pervasive veinlets of calcite overprinted by qtz veins.	1	2	1	1	2	
10		136.70	140.21	Highly alt'd GND. Colour is whitish green, only rounded patches of qtz grains remaining of original texture of GND. Qtz veins still visible as well but selvage is altered into main zone.	2	2	3	1	1	
10		140.21	140.61	Large qtz vein (23cm of core). Relatively low sulphide content						
10		140.61	142.04	GND as at 134.11m. Broken and calcitized.	1	2	1	1	3	
10		142.04	142.53	Less calcite zone w/ 4 large qtz veins. One xeno: fine-grained diorite, long axis parallel to nearby vein (4x2cm)		1	1		1	
10		142.53	143.26	GND as at 134.11m. Broken and calcitized		1	1		1	
10		143.26	145.56	More competent core; v. little calcite		1	1			
10		145.56	146.67	GND as at 134.11m; 50% broken and calcitic	1	2	2		1	
10		146.67	147.15	V. large qtz vein (37cm of core is 'pure' qtz); milky veinlets of calcite are incorporated.					1	
10		147.15	151.54	GND as at 134.11m; 50% broken and calcitic	1	2	1		2	

DRILL LOG LEGEND P2

Date: June 4 - 8, 2005

PAGE 8 of 12

LOGGED BY: M. Stone / K. Whitehead

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS									% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
					Selvages				Sulphides									Oxidation											
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
3	0.5	0.5	45		1.0	cb/q	4	3	2.0			2.0					4.0	3.0										0.00
1	2.5	5.5	45		0.5	q/chl	2	2		10.0		5.0					2.0	1.0			B291728	110.29	111.56	0.163			VA05046971	1.27
1	2.5	5.5	45		0.5	q/chl	2	2		10.0		5.0					2.0	1.0			B291729	110.29	111.56	0.307	PD/CA		VA05046971	1.27
																					B291730	STANDARD 1A		0.987	1A		VA05046971	
1	2.5	4.0	45	25	1.0	q	2		1.0			5.0						4.0			B291731	111.56	112.78	0.244			VA05046971	1.22
1	1.0	1.0	45		0.0					2.0		1.0						5.0			B291732	112.78	114.30	0.024			VA05046971	1.52
1	1.5	4.0	45	55	0.5	q	2	0		5.0		1.0						2.0			B291733	114.30	115.82	0.265			VA05046971	1.52
1	2.0	5.0	45		2.0	q/s	3	1		5.0		2.0						3.0			B291734	115.82	117.35	0.428			VA05046971	1.53
1	2.5	6.0	45	25	4.0	qcnws	4	2		7.0		10.0						4.0			B291735	117.35	118.87	0.158			VA05046971	1.52
																					B291736	BLANK		<0.005			VA05046971	
1	2.5	8.0	45	15	4.0	qcnws	3	2	5.0	10.0	1.0	7.0					0.0	3.0			B291737	118.87	120.40	0.191			VA05046971	1.53
3	0.3	0.3	45		2.0	qcnws	4	1		2.0		1.0						4.0			B291738	120.40	121.98	0.148			VA05046971	1.58
1	1.0	7.0	45	55	1.0	q	3		2.0	8.0		5.0						3.0								silicified zones (old veins)		
1	0.75	2.0	45	30						0.1		7.0									B291739	121.92	123.44	0.160		max sulphide percents	VA05046971	1.52
1	1.00	5.25	45	50						0.1		5.0									B291740	123.44	124.97	0.127			VA05046971	1.53
1	1.25	5.5	45	50						0.1											B291741	124.97	126.49	0.289			VA05046971	1.52
1	1.25	5.5	45	50						0.1											B291742	124.97	126.49	2.070	DUP		VA05046971	1.52
1	0.25	1.0	50																		B291743	126.49	128.02	0.174			VA05046971	1.53
1	1.50	3.5	35	40						0.1											B291744	128.02	129.54	0.084			VA05046971	1.52
1	3.50	6.0	40	45						1.0		1.0									B291745	129.54	130.50	0.452			VA05046971	0.96
1	0.25								10.0			15.0									B291746	130.50	131.06	0.378		qtz pieces; max sulphide percentages	VA05046971	0.56
1	1.00	4.5	40	20						0.1											B291747	131.06	132.59	0.464			VA05046971	1.53
1	1.50	5.75	40	45						0.1		0.1									B291748	132.59	134.11	0.123			VA05046971	1.52
1	1.50	5.75	40	45						0.1		0.1									B291749	132.59	134.11	0.200	PD/CA		VA05046971	1.52
																					B291750	STANDARD 4D		0.416	4D		VA05046971	
1	1.50	8.0	45	60	2.0	wsscnc	3	1		15.0	2.0										B291751	134.11	135.64	0.195			VA05046971	1.53
1	2.50	5.0	35	45	5.0	qcnws	5	1	10.0	10.0		10.0					2.0	1.0			B291752	135.64	136.70	0.640			VA05046971	1.06
1	4.00	5.0	40	25						5.0							3.0				B291753	136.70	138.26	0.271			VA05046971	1.56
3	0.50	1.0	35							2.0							3.0										VA05046971	
1	2.00	4.0	50						20.0			5.0					3.0				B291754	138.26	138.68	0.728			VA05046971	0.42
3	3.00	3.0	30			cb/chl			15.0			2.0					1.0	1.0									VA05046971	
1	1.00	4.0	50	30						10.0		3.0					1.0	1.0			B291755	138.68	140.21	0.240			VA05046971	1.53
																					B291756	BLANK		0.012			VA05046971	
1	23.00	23.0	40						5.0	3.0							3.0				B291757	140.21	140.61	0.044			VA05046971	0.40
1	5.00	9.0	45	55	3.0	q/chl	4	0		5.0		2.0						3.0			B291758	140.61	142.04	0.136			VA05046971	1.43
1	3.00	12.0	45	55	3.0	q/chl	4	0		10.0		5.0						3.0			B291759	142.04	142.53	0.169			VA05046971	0.49
1	1.00	1.0	55		1.0	q	1														B291760	142.53	143.26	0.298			VA05046971	0.73
1	2.00	11.0	40	75	3.0	q/chl	3	0		8.0		5.0						4.0			B291761	143.26	144.78	0.357			VA05046971	1.52
1	2.00	11.0	40	75	3.0	q/chl	3	0		8.0		5.0						4.0			B291762	143.26	144.78	0.238	DUP		VA05046971	1.52
1	2.00	6.0	45		4.0	q/chl	3	0		2.0	0.1										B291763	144.78	145.56	0.270			VA05046971	0.78
1	2.00	8.0	45	30	2.0	q/chl	3	0		10.0		2.0						3.0			B291764	145.56	146.67	0.491			VA05046971	1.11
1	37.00	37.0	60	140	0.0							5.0						3.0			B291765	146.67	147.15	0.139			VA05046971	0.48
1	1.00	3.0	60		3.0	q	4	0		5.0											B291766	147.15	148.30	1.090			VA05046971	1.15
1	1.00	2.5	60		2.0	q/chl	3	1		5.0		5.0						3.0			B291767	148.30	149.35	0.957			VA05046971	1.05
1	4.00	7.5	65	70	2.0	q/chl	2	1		4.0											B291768	149.35	150.88	0.201			VA05046971	1.53
1	4.00	7.5	65	70	2.0	q/chl	2	1		4.0											B291769	149.35	150.88	0.310	PD/CA		VA05046971	1.53
																					B291770	STANDARD 3C		0.081	3C		VA05046971	
1	2.00	6.0	60	50	1.0	q/chl	2	0		4.0											B291771	150.88	151.54	0.178			VA05046971	0.66

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005	PAGE 9 of 12	
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		151.54	153.04	Sheeted vein system w/in calcitic GND.	1	2	1		2	
10		153.04	153.77	More sheeted veins, slightly more rust on microfractures at 30° to CA	2	2	1		1	
10		153.77	154.70	Highly alt'd section (chl) follows 1cm qtz vein (included in last sample). GND texture erased to whitish green homogeneous rock. Veinlets (0.1cm) of pure pyrite. Fractured on one to shiny plate w/ black ox'n product on surface (wipes away easily).	1	3	4		1	
10		154.70	155.45	Minor alt'd GND hits alt'd section from above at 80° to CA. Qtz veins silicified so appears as all selvage		1	2		1	
10		155.45	156.48	Minor alt'd GND. Calcite veinlets pervade and weaken rock, generally at 30°-50°.		1	1	1	2	
10		156.48	159.56	Minor to mod'ly alt'd GND (selvages produce mod alt'n). Calcite vnlets still pervasive & cause breakage generally at 40-60° to CA.	1	2	2		2	
10		159.56	160.57	Carb & sericite alt'd GND. Color is light grey, texture alt'd to more planar (pseudo-foliation), defined by tabular sericite & calcite. One fracture (to 20°) has smeared out pyrite (gold, platey, striated) at 20° to CA w/ calcite/sericite elongate to 25° from the other side (2 episodes movement?). Sample <1% py.		3			3	
10		160.57	161.54	Limonite appears on frac faces, at 20° & 45° to CA; still v. broken.	1	3			2	
10		161.54	163.07	Limonite increases w/in carb/ser alt'd rock so very crumbly. Color is light grey w/ rust-brown along fracs.	2	3			2	
10		163.07	164.59	Cont'd limonite as irregular fracs every few cm to 163.84m. After this, fewer limonized fractures, but calcite still present on them. Xeno 3x2cm f-grained (and foliated) diorite.	1	3			2	
10		164.59	166.12	V. minor alt'n in qtz-rich GND. Diss po & py throughout sample (<2%). Regular fractures @ 50°, lim no longer. 2x1cm xeno 3cm from qtz vn.		3			2	
10		166.12	167.64	Carb/sericite still present along numerous veinlets in random & irregular fractures.		3			2	
10		167.64	169.16	Minor alt'd GND. Two gouge sections @167.85m (4cm) & 168.21m (1.5cm). Alt'd to clay/sand size; no notable slickensides.	1	3		1	2	
10		169.16	171.40	V. minor alt'd GND. Only alt'n is w/in selvages of numerous qtz vns.	1	2	1		2	
10		171.40	172.26	Large qtz vn w/ lenses of massive sulphides. Selvage from 171.4-171.55m. Vein from 171.55-171.87m, selvage from 171.87-172.00m. Vein (3cm) after that w/ 3cm selvage.						
10		172.26	172.78	Alt'd GND w/ 4 veins of massive sulphides.	1	3	3	1	1	
10		172.78	173.62	Mod'ly alt'd GND		2	2		1	
10		173.62	174.29	Mod-highly alt'd GND. Selvages dominate the sample.		3	3			
10		174.29	175.06	Highly alt'd GND. Competent core. Color whitish green to pale grey.		3	3		1	
10		175.06	175.66	Carb/qtz alt'd GND. Crumbly texture, white to light grey in color.						
10		175.66	175.91	Gouge zone. Clay to gravel sized pieces of GND.						
10		175.91	176.15	Chloritized zone w/ 4 qtz veins. Massive pyrite forms in 0.5cm wide lenses adjacent to qtz; Rock effervesces in acid along these lenses - siderite (oxidized pyrite + carbonates)						
10		176.15	177.76	Unaltered GND						
10		177.76	184.40	Alt'd selvages around numerous qtz veins make up bulk of section.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 4 - 8, 2005

LOGGED BY: M. Stone / K. Whitehead

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
									Sulphides								Oxidation				Sample Number			Au (g/T)	sample type	vein comments	CSV	Width (m)
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	5.00	26.0	50		3.0	q/chl	4	1	15.0	10.0		1.0					4.0	4.0			B291772	151.54	153.04	0.163			VA05046971	1.50
1	2.50	10.0	60		1.0	q/chl	2	1	5.0	3.0							4.0				B291773	153.04	153.77	0.456			VA05046971	0.73
1	0.50	0.5	80						2.0		1.0						4.0				B291774	153.77	154.70	0.239			VA05046971	0.93
6	0.10	0.1	50						100.0								4.0											
1	0.50	2.0	50	80	3.0	chl/q	3	0	2.0	5.0	1.0	7.0					1.0				B291775	154.70	155.45	0.829			VA05046971	0.75
																					B291776	BLANK		<0.005			VA05046971	
1	2.00	3.0	40		2.0	q/chl	3	0	7.0			2.0					3.0	1.0			B291777	155.45	156.48	0.292			VA05046971	1.03
1	3.00	8.5	50	70	4.0	chl/q	4	0		10.0	1.0	5.0									B291778	156.48	157.79	0.376			VA05046971	1.31
1	1.20	5.0	50	40	3.0	q/chl	4	0		5.0											B291779	157.79	159.56	0.166			VA05046971	1.77
																					B291780	159.56	160.57	0.321			VA05046971	1.01
1	1.0	2.0	30	40	1.0	q/s	4	0		5.0											B291781	160.57	161.54	0.749			VA05046971	0.97
1	1.0	2.0	30	40	1.0	q/s	4	0		5.0											B291782	160.57	161.54	0.395	DUP		VA05046971	0.97
1	1.5	2.0	30	80	1.0	q/s	3	1		5.0											B291783	161.54	163.07	1.105			VA05046971	1.53
1	1.5	2.5	45	55	1.0	q/s/cb	2	1		8.0	0.1										B291784	163.07	164.59	0.204			VA05046971	1.52
1	1.5	3.0	60	45	2.0	q/s	4	0		10.0	1.0	5.0					1.0				B291785	164.59	166.12	0.251			VA05046971	1.53
1	1.0	3.0	45						0.1	5.0											B291786	166.12	167.64	0.899			VA05046971	1.52
1	1.0	5.0	55	45	2.0	q/s	4	1	3.0	8.0		1.0					5.0				B291787	167.64	169.16	0.653			VA05046971	1.52
1	2.0	7.0	55		1.0	q/s/chl	4	1	1.0	5.0		2.0					3.0				B291788	169.16	170.74	0.191			VA05046971	1.58
1	2.0	7.0	55		1.0	q/s/chl	4	1	1.0	5.0		2.0					3.0				B291789	169.16	170.74	0.442	PD/CA		VA05046971	1.58
																					B291790	STANDARD 4D		0.368	4D		VA05046971	
1	2.5	5.0	40	70	2.0	q/s/chl	4	1	2.0	8.0		5.0					3.0	3.0			B291791	170.74	171.40	0.301			VA05046971	0.66
1	32.0	32.0	60		30	q/s/chl	5	1	20.0	5.0		10.0					4.0	1.0			B291792	171.40	172.26	7.760			VA05046971	0.86
6	0.6	2.4	60						10.0			75.0					4.0	0.0			B291793	172.26	172.78	9.370		in alt'n zone - selvages not distinguishable	VA05046971	0.52
1	1.0	2.0	60																							adjacent to sulph veins		
1	1.0	4.0	70	130	10	q/s/chl	4	0	1.0	5.0		5.0									B291794	172.78	173.62	0.169			VA05046971	0.84
1	0.5	3.0	55		10	q/s/chl	5	0	6.0	10.0		4.0					3.0				B291795	173.62	174.29	0.373			VA05046971	0.67
																					B291796	BLANK		0.030			VA05046971	
1	1.0	1.0	55						0.1	5.0		0.1					4.0				B291797	174.29	175.06	2.130			VA05046971	0.77
1	0.8	1.6	60		1.0	q/s/chl	4	0	0.1	8.0											B291798	175.06	175.66	0.136			VA05046971	0.60
																					B291799	175.66	175.91	0.473			VA05046971	0.25
1	1.0	3.0	45		16.0	chl/q/s	5	0	15.0								3.0				B291800	175.91	176.15	1.645			VA05046971	0.24
1	1.0	5.0	45		10.0	chl	5	0	1.0	5.0											B291801	176.15	177.76	0.393			VA05046971	1.61
						s	5																					
						cb	2																					
1	1.0	5.0	45		10.0	chl	5	0	1.0	5.0											B291802	176.15	177.76	0.562	DUP		VA05046971	1.61
						s	5																					
						cb	2																					
1	20.0	20.0	45		50.0	chl	4		30.0								4.0				B291803	177.76	178.30	0.868			VA05046971	0.54
						s	4																					
						cb	4																					
1	1.0	2.0	45		1.0	q	3	0		3.0		1.0									B291804	178.30	179.83	0.135			VA05046971	1.53
						chl	2																					
3	0.5	0.5	20		1.0	cb	3	0	0.0												B291805	179.83	181.36	0.280			VA05046971	1.53
						q	3																					
1	1.0	4.0	45		0.5	q	2	0		12.0	1.0						2.0				B291806	181.36	182.88	0.398			VA05046971	1.52
1	1.0	3.2	50		7.0	q	5	0		5.0											B291807	182.88	184.40	0.037			VA05046971	1.52
						s	2																					
						chl	3																					

DRILL LOG LEGEND P1	DATE: June 4 - 8, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-279C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; SAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		185.93	186.83	Rounded xeno w/ ragged edges, 3x2cm, at 186.25m.						
10		186.83	188.07	Minor alt'd GND. V. broken up due to calcite and limonite pervading along microfractures and throughout matrix of GND.	1	3	1	1	1	
10		188.07	188.98	Minor alt'd GND. Lim & calcite on microfractues. Xenolith at 188.65m, 3x2cm.	1	2		1	1	
10		188.98	190.50	GND w/ calcite throughout matrix and microfractures. Very broken and crumbly core		2	1	2	2	
10		190.50	201.17	Unalt'd GND w/ qtz and qtz/carb veins. At 190.62, rounded xeno of fine-grained diorite w/ 2mm rxn rims. Ox'd py (90%) + aspy (10%) concentrated in 10cm zones: at 190.90m-191.00m and at 192.02-192.12m. No affiliated veinage. Xenoliths at: 194.5m, 195.4m, and 196.55m.		1				

DRILL LOG LEGEND P2

Date: June 4 - 8, 2005

PAGE 12 of 12

LOGGED BY: M. Stone / K. Whitehead

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)
Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	2.0	5.5	50		15.0	chl	4		10.0					10.0							B291808	184.40	185.93	0.166			VA05046971	1.53
						q	2																					
						s	3																					
3	2.0	5.5	50		15.0	chl	4		10.0					10.0							B291809	184.40	185.93	0.138	PD/CA		VA05046971	1.53
						q	2																					
						s	3																					
																					B291810	STANDARD 2B		3.020	2B		VA05046971	
1	2.0	2.0	50		10.0	chl	4		10.0	10.0																		
						q	3																					
						s	3																					
1	1.2	1.2	70		12.0	chl															B291811	185.93	186.83	0.107			VA05046971	0.90
						q																						
3	0.2	2.0	30	70	4.0	chl																						
						q																						
						s																						
1	1.0	1.0	45		1.0	q	2	0				1.0						5.0			B291812	186.83	188.07	0.057			VA05046971	1.24
						s	2																					
																					B291813	188.07	188.98	0.022			VA05046971	0.91
1	4.0	4.0			20.0	chl	4	0				5.0						4.0			B291814	188.98	190.50	4.490		angles not dist. b/c qtz in pieces.	VA05046971	1.52
						s	4																					
1	0.5	0.5	50		0.2	q	2	0	0.0												B291815	190.50	192.02	0.063			VA05046971	1.52
																					B291816	BLANK		<0.005			VA05046971	
3	0.5	2.0	45		1.5	q	3	0	3.0	5.0		1.0					2.0	4.0			B291817	192.02	193.55	0.052			VA05046971	1.53
						chl	2																					
						cb	2																					
6	0.5	0.5	45		4.0	chl	4	3				10.0														nice, euhedral aspy, up to 1.3cm long			
1	0.5	1.0	60		1.5	chl	2	0	2.0	10.0							5.0				B291818	193.55	195.07	0.072			VA05046971	1.52
						q	3																					
1	1.5	5.0	45	60	1.0	q	3	0		8.0	1.0	5.0						3.0			B291819	195.07	196.60	0.857			VA05046971	1.53
						chl	2																					
1	2.0	5.0	45		2.0	q	3		5.0	3.0											B291820	196.60	198.12	0.414			VA05046971	1.52
						chl	1																					
1	2.0	8.0	45		0.5	q	1			3.0		1.0						2.0			B291821	198.12	199.64	3.380			VA05046971	1.52
1	2.0	8.0	45		0.5	q	1			3.0		1.0						2.0			B291822	198.12	199.64	1.130	DUP		VA05046971	1.52
1	1.5	11.0	45		0.5	q	2		2.0		1.0	8.0						0.0			B291823	199.64	201.17	0.208			VA05046971	1.53
																							EOH					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-280C

PROJECT: Dublin Gulch - 1735

DATE STARTED:	DATE COMPLETED:
06-Jun-05	10-Jun-05

LOGGED BY:
Kristian Whitehead & Terry Croteau

CONTRACTOR:
Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 6.10m
Deviation:
Casing: 6.10m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

FROM	TO	LITHOLOGY
6.10	202.78	Granodiorite

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

GROUND ELEVATION:

BEARING: 000 | DIP: -50°

COORD SYSTEM: NAD 27:	EASTING: 459107	NORTHING: 7099141
COORD SYSTEM: NAD 83:	EASTING: 458988	NORTHING: 7099328
NAD 27 (CORRECTED for historic grid):	EASTING: 459077	NORTHING: 7099151

SECTION LINE(historic grid)

SAMPLING DETAILS

Sample Sequence: B292501 - B292559
Requisition #: MASP448STRGOL.05Q — Date Shipped: 10-June-05
Lab Record #: VA05047189 — Date Received: 27-June-05

Sample Sequence: B292560 - B292707
Requisition #: MASP448STRGOL.05Q — Date Shipped: 13-June-05
Lab Record #: VA05047825 — Date Received: 30-June-05

Duplicates:	B292502, B292522, B292542, B292562, B292582, B292602, B292622, B292642, B292662, B292682, B292702
Preparation Duplicate/ Check Assay:	B292509, B292529, B292549, B292568, B292589, B292609, B292629, B292649, B292669, B292689
Standards:	B292510, B292530, B292550, B292570, B292590, B292610, B292630, B292650, B292670, B292690
Blanks:	B292516, B292536, B292556, B292576, B292596, B292616, B292636, B292656, B292676, B292696

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	DIP (+27 Corr)
50	333.0	50.7	359.0	000.0
125	333.3	51.3	359.3	000.3
207	334.7	51.4	000.7	001.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005 PAGE 1 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; QIOR = 25; MGD = 30; APL = 40; FLCQ = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-6.10			Overburden - Drill Casing; no recovery						
10	6.10-202.78			GND 40% qtz, 20% kspar, 15% bt, 10% Hal	3			1		
10		6.10	10.67	Broken GND: Core is extremely weathered and broken. Most pieces are angular, but some subangular - rounded. Sugary textured GND also present throughout. Lim is pervasive, and recovery is poor						
10		10.67	12.19	GND alterations trends to more clay rich gouge. Qtz eyes present with GND frags. Lim is pervasive.	3			2		
10		12.19	13.72	GND becomes slightly altered, lim is pervasive. @12.39m, GND becomes more fractured and sugary textured, lim staining becomes more intense. Veinlets present in fractured core; angles are indeterminate.	2			1		
10		13.72	14.02	Core is fractured and broken. Lim is pervasive. Clay alteration is less intense. Veinlets in section appear to be running at 35° to CA	2			1		
10		14.02	15.34							
10		15.34	16.50	Gouge, clay and sand w/ minor gravel pieces. Limonite is heavy on fracs. Zone of hydrothermal alteration. Limonite abruptly ends @ 16.90m	3	1		3		
10		16.50	16.76							
10		16.76	18.29	Core is extremely broken w/ poor core recovery. Aspy can be seen as thin coating on what looks like fractured surfaces	2					
10		18.29	19.29							
10		19.29	21.50	At ~19.20m: a fault/alteration zone. Evident from sandy and clay residue on core. Looks like aspy is remnant, but oxidized	2	1		1		
10		21.50	26.63	GND has bleached intervals, core has suffered some decay from sericite of fracs as evidence, broken core is demonstrating aspy oxidation and crystals	2	2	1	1	0	
10		26.63	31.37	Core becomes intensely oxidized to a dull brown colour, limonite is on fracs and moderately pervasive. Sericite is abundant on fracs and is pervasive. Chlorite is weak to moderate. Core is soft w/ oxidized aspy on fracture surfaces. Veins are essentially relict w/ oxidized aspy. Mafics are scarce and core crumbles when scratched in sections	4	3	2	1		
				From 28.63m to 28.60m, an orangey-gold coloured clay seam w/ oxidized aspy & possibly py. Contact @ 28.69m preserved @ 42° to C.A.	3	2		4		
				Another clay seam from 29.05 to 29.19m. Clay is uniform, light dull brown, w/ minor orangey-gold colours on contact. Uncertain if contact @ 29.19 is preserved but @ 35° to C.A.	3	2		5		
				Clay seam from 29.62 to 29.84m; core is orangey tiger colour. Oxidized and intact aspy and py	3	2		4		
				Clay seam from 30.48 to 30.91m; vein is relict by aspy veining, @~50°. Core is abundant w/ limonite	5	1	1	3	1	
10		31.37	31.50							
10		31.50	33.46	At 31.50m limonite completely and abruptly ends. GND is altered to a grey sericite rich, soft core. Mafics are still present, yet less in abundance than in unaltered GND. Sericite is pervasive and abundant on fracs and vein contacts. Qtz veins are somewhat intact w/ diss oxidized/unaltered aspy predominant. Core is essentially light grey in colour and uniform	4	4	1	2	1	
10		33.46	34.69							
10		34.69	35.08	Grey-white clay gouge alteration zone. No contacts preserved, some minor dissem ox'd aspy	4	3	1	4	1	
10		35.08	36.36							
10		36.36	38.95	At 36.36m, fault/slickensides @ 30° to CA, aspy/qtz vein, aspy ~25%, fault appeared to cut through vein, not activate along vein						
10		38.95	39.43	GND loses its mafics, core is dull greenish grey w/ sericite and chlorite present	3	2	2			
10		39.43	39.70	Semi massive aspy + py qtz vein. Sulphides are somewhat concentrated @ centre of vein w/ stringers/blebs running outwards. Py content ~3-5%, aspy ~40-45%. Qtz remainder w/ qtz being an opaque white						
10		39.70	40.49	GND is essentially digested to qtz eyes and sericite clay (good recovery). Core has a light green chlorite hue and has relict aspy and py vein/veinlets. 39.70 contact @ 30°, 40.49 contact has slicken lineations indicating a fault @ 40°	5	5	2	5		
10		40.49	40.63							
10		40.63	40.65	One 2.25cm thick qtz vein w/ disseminated aspy + py. angle 35-40°. Photo of area included.						
10		40.65	41.03							
10		41.03	43.54	GND continues to be devoid of mafics; sericite and chlorite to a minor state dominate, core is bleached with powdery, light grey colour	3	3	1			
				From 42.14-42.35m, core is altered to white-grey clay and qtz eyes. Slickensided surface @~50° to CA. Surface had minor aspy 'slickened'.	3	4	1	4		
10		43.54	44.20	GND alteration zone, begins with clay predominant and then progresses to clay/ qtz eyes and broken core. All core is bleached with little to no mafics. Aspy is dissem w/ py. Sericite abundant on fracs and mod'ly pervasive	3	3	1	2		
10		44.20	46.50							
10		46.50	47.42	Hydrothermal alt'n zone (gouge). Sericite/qtz eyes/ grey-white clay w/ dissem aspy.	3	3		3		
10		47.42	48.15	Alt'd / bleached core as progressing from above. Gouge unit @47.85-47.93m. Sulphides (semi-massive) pyrite (30%), aspy (5-10%).	3	3	2	1		
10		48.15	50.09							
10		50.09	50.20	Clay gouge unit. Clay is light grey with aspy ox'd within (~5%)	3	3	1	5		
10		50.20	53.23							
10		53.23	53.38	Gouge, broken core, alteration zone. Core is light grey abundant w/ sericite, bleached	3	3	1	3	2	
10		55.38	55.59	Chlorite alteration zone. Core is light grey white w/ green hue. Sericite abundant	3	3	2			
10		55.59	56.39	Gouge/qtz eyes w/in semi-competent hydrothermal alteration zone. Core is light grey w/ pervasive sericite and on frac. Minor carbonates. Trace chlorite	3	3		2	1	
10		56.39	56.61	Medium grey uniform clay, looks like aspy clay. Directly adjacent @ 56.53-56.61m a qtz vein w/ aspy stringers	3			5		
10		56.61	57.09	Gouge alteration zone, core is white grey w/ minor green hue (chlorite). Qtz eyes, sericite dominant	3	4	1	4		

DRILL LOG LEGEND P2

Date: June 6 - 10, 2005

PAGE 2 of 10

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, ob = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
										Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
0																															
0																						B292501	6.10	7.62	0.088			VA05047189	1.52	
0																						B292502	6.10	7.62	0.062	DUP		VA05047189	1.52	
0																						B292503	7.62	9.14	0.102			VA05047189	1.52	
0																						B292504	9.14	10.67	0.143			VA05047189	1.53	
0																						B292505	10.67	12.19	0.199			VA05047189	1.52	
3	1	0.2	0.2										5.0									B292506	12.19	13.72	1.020		Veinlets are broken and difficult to orient	VA05047189	1.53	
1	1	0.2	0.2										3.0									B292507	13.72	14.02	0.332		Veinlets are broken and difficult to orient	VA05047189	0.30	
																						B292508	15.24	16.76	0.430			VA05047189	1.52	
																						B292509	15.24	16.76	0.509	PD/CA		VA05047189	1.52	
																						B292510	STANDARD 6F		2.650	6F		VA05047189		
1	1	0.75											0.1									B292511	16.76	18.29	0.122			VA05047189	1.53	
1	6	0.25	0.25	40									50.0									B292512	18.29	18.90	0.161			VA05047189	0.61	
										0.1	1.0											B292513	18.90	19.81	0.332			VA05047189	0.91	
1	1	0.25	0.25	30	35								1.0					1.0				B292514	19.81	21.34	0.276			VA05047189	1.53	
													3.0									B292515	21.34	22.86	0.145		QTZ PIECES; aspy tr to 3%	VA05047189	1.52	
																						B292516	BLANK		<0.005			VA05047189		
3	1	0.75	1.5	40	55								5.0									B292517	22.86	24.38	0.450		aspy: tr. to 5%	VA05047189	1.52	0.225
7	1	1.0	3.5	35	45	0.1	1						5.0									B292518	24.38	25.91	0.231		aspy: tr. to 5%	VA05047189	1.53	0.356
7	1	1.5	3.25	35	85								3.0									B292519	25.91	27.76	0.336		aspy: tr. to 3%	VA05047189	1.85	0.365
4	1	0.5	1.5	45						1.0			5.0									B292520	27.76	29.05	0.241		py: tr. to 1%; aspy: tr. to 5%	VA05047189	1.29	0.531
										1.0			3.0									B292521	29.05	30.48	0.208		py: tr. to 1%; aspy: tr. to 3%	VA05047189	1.43	0.471
										1.0			3.0									B292522	29.05	30.48	0.283	DUP	py: tr. to 1%; aspy: tr. to 3%	VA05047189	1.43	
										1.0			8.0					5.0				B292523	30.48	31.50	0.418			VA05047189	1.02	0.539
										0.1			10.0					5.0				B292524	31.50	32.00	0.503			VA05047189	0.50	
2	1	0.5	1.0	50	40					0.1			2.0					4.0				B292525	32.00	33.53	0.299			VA05047189	1.53	0.449
										0.1			0.1					4.0				B292526	33.53	34.69	0.483		pieces	VA05047189	1.16	0.601
													1.0									B292527	34.69	35.06	0.169		pieces	VA05047189	0.37	
2	1	0.25	0.5	45						0.1		5.0										B292528	35.06	36.58	0.263			VA05047189	1.52	0.685
2	1	0.25	0.5	45						0.1		5.0										B292529	35.06	36.58	0.261	PD/CA		VA05047189	1.52	
																						B292530	STANDARD 5E		1.250	5E		VA05047189		
13	1	1.0	8.5	45	75					1.0			25.0									B292531	36.58	38.10	0.267			VA05047189	1.52	0.372
4	1	0.75	2.25	50						0.1	0.1		15.0					1.0				B292532	38.10	39.43	0.191			VA05047189	1.33	0.35
1	1	11.0	11.0	45	50					5.0			45.0					2.0				B292533	39.43	39.70	0.249		includes sulph veins	VA05047189	0.27	0.371
										1.0			10.0					2.0				B292534	39.70	40.49	0.166		clay altered	VA05047189	0.79	
																						B292535	40.49	41.25	0.060			VA05047189	0.76	
																						B292536	BLANK		<0.005			VA05047189		
1	1	3.0	3.0	50		0.1	1						1.0									B292537	41.25	42.42	0.103			VA05047189	1.17	0.229
4	1	1.0	2.0	45		0.1	1						5.0									B292538	42.42	43.54	0.116			VA05047189	1.12	0.177
													5.0									B292539	43.54	44.20	0.157		qtz pieces	VA05047189	0.66	
4	1	0.75	2.25	55	50								1.0									B292540	44.20	45.72	0.162			VA05047189	1.52	0.334
2	1	0.5	1.0	55	60								3.0									B292541	45.72	46.95	0.096			VA05047189	1.23	
2	1	0.5	1.0	55	60								3.0									B292542	45.72	46.95	0.110	DUP		VA05047189	1.23	0.195
2	1	1.25	1.75	45									5.0									B292543	46.95	48.15	0.072		alteration zone	VA05047189	1.20	0.212
2	1	0.5	0.75	50									2.0									B292544	48.15	48.77	0.086			VA05047189	0.62	
1	1	0.25	0.5	30									2.0									B292545	48.77	50.21	0.062			VA05047189	1.44	0.243
4	1	1.0	1.75	40	55								2.0									B292546	50.21	51.82	0.049			VA05047189	1.61	0.252
2	1	0.25	0.5	50	60																	B292547	51.82	53.38	0.074			VA05047189	1.56	0.252
1	4	1.0	1.0	40									3.0					1.0				B292548	53.38	54.86	0.041			VA05047189	1.48	0.226
1	4	1.0	1.0	40									3.0					1.0				B292549	53.38	54.86	0.041	PD/CA		VA05047189	1.48	
																						B292550	STANDARD 2B		2.870	2B		VA05047189		
1	1	0.5	0.5	30									0.1									B292551	54.86	55.33	0.026			VA05047189	0.47	0.196
4	1	4.0	5.75	35	40					2.0			2.0									B292552	55.33	56.39	0.149			VA05047189	1.06	
1	1	4.5	4.5	40									3.0									B292553	56.39	57.91	0.128			VA05047189	1.52	0.214

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005 PAGE 3 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MQD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		57.09	57.91	Core continues to be bleached, devoid of mafics, sericite rich, yet competent area caught between 2 hydrothermal alt'n zones. Dissem aspy (1%) and py (tr.)	3	3		1		
10		57.91	58.91	Gouge alteration zone, core is white grey w/ minor green hue (chlorite). Qtz eyes, sericite dominant	3	3	1	3		
10		58.91	61.00	Core is altered/bleached, yet competent. Core is light grey w/ green (chl) hue. Core is easily scratched, little to no mafics. Sericite on fracs, and moderately pervasive	3	3	1	3.0		
10		61.00	61.32							
10		61.32	61.71	Core has been etched and bleached, however, mafics are still intact. Salt/pepper appearance		2	1	1		
10		61.71	62.16							
10		62.16	62.48	Grey white clay seam perhaps fault gouge due to abundant slickensides throughout immediate section		3		5		
10		62.48	62.59	Core has been etched and bleached, however, mafics are still intact. Salt/pepper appearance		2	2	1		
10		62.59	63.60							
10		63.60	66.89	At 63.60m is a slickenside surface w/ aspy and ox aspy on contact @ 45° to CA. Another, at 63.92m, slickenside surface @40° to CA.						
10		66.89	68.48	Altered GND, core is bleached to light grey, greenish hue. Minor aspy dissem bits probable that a vein was proximal only lost in recovery. Core becomes gouge/med grey clay. Core is v. broken w/ poor core recovery. Carb in form of veinlets. At 68.63m, a slickenside surface @40° to CA		2	2	1	1	
10		68.48	70.41	Chloritized, altered, bleached GND. Core has slight green hue (chlorite). Core is sericite rich, core can easily be scratched, contains several qtz/carb veins/veinlets @ 68.78: slickenside, 60° @ 69.76: slickenside, 30°		4	2			
10		70.41	72.60							
10		72.60	75.26	Altered GND. Bleached to light grey, green; essentially the selvage around a qtz/carb and sulphide vein/stringers @ 72.68-72.69m, @ 40° to CA. @ 72.60m: slickenside, 35-40° to CA. At 74.73m, slickensides @ 25°-30° to CA.						
10		75.26	75.37	Altered chloritized GND. Selvage around a 0.5cm wide calcite vein		4	2			
10		75.37	76.00							
10		76.00	77.46	Clay gouge w/ qtz eyes, occasional pieces (some w/ slickenside surfaces). Clay is med grey w/ minor sulphide oxidation mixed in	4	3	1	5	1	
10		77.46	81.03	At 77.72m, a slickenside surface, @40° to CA. At 80.60m, slickenside surface @60° to CA, noted that area is altered w/in 2-3cm away		2	2		1	
10		81.03	81.70	Alteration selvage leading to fault gouge @ 81.70 - 81.87m, alteration selvage is light grey-green (chlorite) abundant w/ sericite and devoid of mafics		4	2	0		
10		81.70	82.30	Carbonate stringers w/ aspy and carb veins running ~50° to CA w/in other side of above mentioned alteration selvage from gouge focal point		4	2		5	
10		82.30	82.32	A 2.5cm wide carbonate qtz vein @ 25° to CA w/ ~5% aspy.						
10		82.32	82.56	Alteration selvage continues. @82.56 - slickenside @ 60° to C.A., aspy. on contact surface		4	2		1	
10		82.56	82.74	Clay gouge, light grey clay w/ qtz eyes, aspy disseminated (~5%); contact @ 82.74m is slickensided @ 20° to CA w/ selvage alteration continuing to ~82.94m		4	1	5		
10		82.74	82.83	A qtz/carb vein (1.25cm thick w/ py and aspy) @ 30° to CA is on a site of a fault indicated by slickensides (@ same 30° angle)						
10		82.83	85.69	@85.07: a slickenside, 65°-70° to CA @85.07: a 1.5cm thick qtz/aspy vein, 65°-70° to CA. Aspy ~20% w/ 10cm wide (either side) chlorite bleached sericite prevalent alteration selvage. Trace py.						
10		85.69	88.94	Core is very broken, yet unaltered. Abundant 'vein like' selvages which are typically @ 40-50° to CA. Broken core is occurring commonly on these vein like selvages, which demonstrate aspy. Core would have an estimate of ~1-3% aspy. Some minor chlorite staining on frac surfaces and occasional slickenside pieces						
10		88.94	89.22	Altered GND. Core is bleached, sericite rich, chloritic stained. Minor mafics visible. Qtz eyes beginning to appear. Aspy stringer/veinlet x-cutting core @ 40-55° to CA, yet sulphides are oxidized mostly	3	3	1	1		
10		89.22	89.95	Core is v. broken, but pieces are demonstrating slickensides on veneers of aspy/calcite. @ 89.92m, slickenside surface of aspy coating. Possible py, 50° to CA.						
10		89.95	90.21	@89.95m: slickenside surface of aspy coating. Possible py, 50° to C.A. Altered selvage GND. Core is light grey-white w/ green (chl) hue. Soft core, abundant sericite w/ trace dissem aspy.		3	1	1		
10		90.21	90.28	White to light grey clay gouge. Qtz eyes		4	1	5		
10		90.28	90.68	Core is v. broken with slickensides on pieces w/ aspy & py & chl on contact surfaces						
10		90.68	91.85	Core is v. broken and is breaking down selvages/veinlets @ 40-60° to CA w/ py and aspy on frac surfaces w/ a lesser extent qtz and carb (sheeted veinlet system may be interpreted)						
10		91.85	92.96							
10		92.96	96.01	GND continues to retain sheeted vein like system. Typical vein/selvage spacing ~ 5cm, and ~55°-60° to CA.						
				From 94.25 to 94.53m, GND becomes slightly bleached and mafics reduce to half regular percentage, w/ a 1cm thick qtz vein, 40° to CA.		1	1			
10		96.01	96.54							
10		96.54	96.80	Core is altered to v. soft. 50% clay, 50% core, core is bleached, yet 5% mafics remain. Chlorite presence gives green hue to colour @ 96.70m: slickensides @ 40-45° to CA.		4	1	3		
10		96.80	97.54	Py and aspy thin frac coating on frac which is along core axis						
10		97.54	98.62							

DRILL LOG LEGEND - P2

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL										Oxidation					Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	Sulphides: pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation: oxide	scorodite	biotite	other			From	To						
																							B292554	57.91	58.91	0.067		clay zone	VA05047189	1.00	0.211
																							B292555	58.91	59.44	0.067		clay zone	VA05047189	0.53	0.273
																							B292556	BLANK		<0.005			VA05047189		
2	1	0.75	1.25	40	50								5.0										B292557	59.44	60.96	0.037			VA05047189	1.52	
1	1	1.0	1.0	50									1.0										B292558	60.96	62.16	0.012			VA05047189	1.20	0.286
													3.0										B292559	62.16	62.48	0.008		gouge	VA05047189	0.32	
3	1	0.75	1.25	50	35								3.0										B292560	62.48	64.01	0.028			VA05047825	1.53	0.16
3	1	1.0	1.75	50	40																		B292561	64.01	65.53	0.061		qtz + qtz/carb veins	VA05047825	1.52	0.157
3	1	1.0	1.75	50	40																		B292562	64.01	65.53	0.039	DUP	qtz + qtz/carb veins	VA05047825	1.52	
4	1	0.5	2.0	50	60								0.1										B292563	65.53	67.02	0.037			VA05047825	1.49	0.137
																							B292564	67.02	68.58	0.035		broken core/ gouge	VA05047825	1.56	0.165
1	1	0.25	0.25		35					2.0			0.1										B292565	68.58	70.10	0.032			VA05047825	1.52	0.147
1	4	0.25	0.25	35						2.0			0.1																		
2	1	0.5	1.0	40						25.0					1.0								B292566	70.10	70.41	0.076		qtz + carb + sulph veins	VA05047825	0.31	0.174
3	1	0.25	0.75	50	60					0.1													B292567	70.41	71.63	0.043			VA05047825	1.22	
6	1	0.50	3.25	50									5.0										B292568	71.63	73.15	0.049		qtz + qtz/carb veins	VA05047825	1.52	0.231
6	1	0.50	3.25	50									5.0										B292569	71.63	73.15	0.059	PD/CA	qtz + qtz/carb veins	VA05047825	1.52	
																							B292570	STANDARD 3C		0.087	3C		VA05047825		
8	1	0.5	2.25	50									2.0										B292571	73.15	74.68	0.031			VA05047825	1.53	-0.194
1	4	0.75	0.75	50									2.0										B292572	74.68	75.26	0.028			VA05047825	0.58	0.196
2	4	0.5	0.75	50																			B292573	75.26	76.20	0.032			VA05047825	0.94	
																							B292574	76.20	77.46	0.034		broken core	VA05047825	1.26	0.163
9	1	0.5	2.75	40	50					0.1			0.1										B292575	77.46	79.18	0.037			VA05047825	1.72	0.211
																							B292576	BLANK		<0.005			VA05047825		
5	1	0.5	1.75	50		2.0	3			0.1			0.1										B292577	79.18	80.40	0.049			VA05047825	1.22	0.139
4	1	0.5	2.0	40		1.0	2			0.1			0.1										B292578	80.40	81.03	0.054			VA05047825	0.63	0.124
1	4	0.25	0.25	40						0.1			0.1																		
2	1	0.25	0.5	50									8.0										B292579	81.03	82.30	0.072			VA05047825	1.27	
2	4	2.0	2.25	50									5.0																		
1	3	1.5	1.5	30						0.1			1.0										B292580	82.30	82.94	0.068			VA05047825	0.64	
1	6	0.25	0.25	40		1.0	2			0.1			1.0										B292581	82.94	83.82	0.079			VA05047825	0.88	
1	6	0.25	0.25	40		1.0	2			0.1			1.0										B292582	82.94	83.82	0.112	DUP		VA05047825	0.88	
2	1	1.0	2.0	55	70					1.0			5.0										B292583	83.82	85.34	0.079			VA05047825	1.52	
4	1	0.5	2.0	40		0.5	2						0.1										B292584	85.34	86.87	0.073		4 qtz veins and pieces	VA05047825	1.53	
2	1	0.25	0.5	45		1.0	2						3.0										B292585	86.87	88.39	0.082		2 veins and qtz pieces	VA05047825	1.52	
3	1	0.5	2.0	45	50	1.0	2						3.0										B292586	88.39	89.92	0.086		3 veins and pieces	VA05047825	1.53	
4	1	0.5	1.75	40	45	1.0	2						1.0										B292587	89.92	90.68	0.066			VA05047825	0.76	
										1.0			2.0										B292588	90.68	91.44	0.076		v. broken core	VA05047825	0.76	
										1.0			2.0										B292589	90.68	91.44	0.075	PD/CA		VA05047825	0.76	
																							B292590	STANDARD 5E		1.46	5E		VA05047825		
										1.0			1.0										B292591	91.44	92.96	0.075		v. broken core	VA05047825	1.52	
5	1	0.25	1.25	50		1.0	2			10.0			5.0										B292592	92.96	94.49	0.119		py: tr. to 10%	VA05047825	1.53	
4	1	0.25	1.0	45		1.0	2						2.0										B292593	94.49	96.01	0.092			VA05047825	1.52	0.408
										0.1			1.0										B292594	96.01	96.90	0.145		broken core	VA05047825	0.89	0.235
10	1	1.0	6.25	50		1.0	2			2.0			90.0										B292595	96.90	99.06	0.051		aspy: tr. to 90%	VA05047825	2.16	0.218

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005	PAGE 5 of 10	
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		98.62	102.11	Core is abundant w/ fracs (45°-50° to C.A.), common w/ slickensides of aspy/py thus adding to the amount of sheeted veins accounted for.						
10		102.11	117.06	Sheeted veins continue through entire unit, save for bleached altered zone (103.63 - 104.19). Angles typically 40-55° to CA w/ widths ranging from <0.25cm to 0.50cm. Dissem aspy as the predominant sulphide w/ tr po, tr-2% py. Slickensides are common on frac surfaces w/ sulphides on those contacts. Occasional chlorite staining on fracture surface						
				From 103.63 to 104.19m, GND is bleached ,altered zone w/ clay gouge @ ~ 103.74 - 103.89. gouge/pieces of core shows aspy on qtz surfaces, clay is light grey-white	1	2	1	3		
				At 113.53, a 2cm carbonate vein w/ trace aspy (30° to CA) is cross-cut by an aspy veinlet, @45° to CA.						
				From 115.82 to 115.92m, core is altered and bleached, with oxidized aspy, core is easily scratched, sericite is minor to moderate, oxidized aspy veinlets (~5-8%)	2	2	1	1		
10		117.06	117.20	Continued alteration unit as above, core is bleached, however mafics remain, sericite is moderate and grey-looking ox'd aspy is ~5%. Core is easily scratched by a nail, minor clay, some carb veinlets present. Sheeted veining continues at 5-10cm spacing w/ veins/selvages typically 35-50° to CA and <0.75cm wide. Slickensided frac surfaces remain common w/ aspy on surfaces	2	2	1	1	2	
10		117.20	121.42							
10		121.42	121.63	Alteration zone, core is bleached to little or no mafics, sericite and chlorite are prevalent.						
10		121.63	123.44							
10		123.44	129.00	GND begins to bleach out and carbonates begin to pervade the core by coating and veinlets. Core progressively bleaches to ~123.70m where it remains constant until ~129.00m. Core can easily be scratched, qtz veins tough to see because digested; core displays mafics only. Salt and pepper appearance due to bleaching/sericite clay w/ minor chlorite hue. Aspy is present as med-dark grey oxidized veinlets. Core appears as "acid etched"		2	1		2	
10		129.00	130.19							
10		130.19	130.55	Gouge/clay seam, digested bleached core, although some mafic-retained zones. Sericite/chlorite present. Core is v. soft. Contact @130.19m, @20° to CA, cutting veins that are @~ 50°-60° to CA, carbonates present as stringers/veinlets	3	1	1	2		
10		130.55	131.30							
10		131.30	132.02	V. broken bleached/alt'd core. Core reduced to sandy sericite clay w/ some gravel sized pieces. **Note:** still remains a sheeted vn system, vning intensity ebbs & flows. From ~132.0-137.0m: core has a high amount of sheeted vns/meter (~1 per 5cm)		3	2	2	2	
10		132.02	137.09							
10		137.09	137.15	A chlorite/sericite/altered/stained core w/ almost rectangular carbs pass through the core @ ~40-45° to CA. Core immediately surrounding is mafic devoid. No visible sulphides associated.		2	2		2	
10		137.15	138.75	Core is bleached & alt'd to a mafic free, chlorite/sericite prevalent core. Core has greenish hue. Dissem py & aspy around relict selvages/vns/vnlets.		3	2			
10		138.75	139.05							
10		139.05	140.12	Core becomes alt'd grey w/ no visible mafics, sericite & chlorite prevalent. Calcite stringer initially present although they somewhat follow ~50° to CA w/ larger veins.		2	2		2	
10		140.12	140.33	Semi-massive to massive py (85%), aspy (15%) vein. Contact angle @140.33m is @~70° to CA.						
10		140.33	140.60	Grey clay gouge is rich w/ dissem sulphides, although they have been mostly oxidized & thus difficult to discern concentration or percentages of py & aspy. Looks like aspy is prevalent based on grey color & sparkles. Contact @ 140.60m is @30° to CA.						
10		140.60	144.27	Continues to be alt'd & sheeted vn system remains continuous onwards. GND alteration is notably increasing in chlorite, and core is displaying more prominent green color w/ biotite fading.						
10		144.27	144.54	Alt'd GND core is bleached w/ little to no mafics. Core has green hue speckled w/ carb spots (2-5%). Sericite & chlorite present; Core is easily scratched, and is essentially the selvage of py & aspy & sphalerite. Qtz vein @144.53m @40° to CA. Sheet vn system continues.		2	2	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, qb = carbonate, b = biotite, pc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 6 - 10, 2005

LOGGED BY: Kristian Whitehead, Terry Croteau

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL																Interval						
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
																						B292596	BLANK		<0.005			VA05047825		
9	1	0.75	3.75	45	50	1.0	2			0.1			90.0									B292597	99.06	100.58	0.062		aspy: tr. to 90%	VA05047825	1.52	0.222
2	4	0.1	0.2	45	50																										
4	1	0.5	2.5	50	55	1.0																B292598	100.58	101.05	0.066			VA05047825	0.47	0.29
2	1	2.0	3.0	45	50	1.0	2			2.0			50.0									B292599	101.05	101.66	0.116		aspy: 2-50%	VA05047825	0.61	
4	1	0.5	2.25	45	55	0.5	1			1.0			50.0									B292600	101.66	103.63	0.08		aspy: 2-50%	VA05047825	1.97	0.299
													50.0									B292601	103.63	104.19	0.058		aspy: 2-50% gouge (clay) w/ qtz pieces	VA05047825	0.56	0.49
													50.0									B292602	103.63	104.19	0.086	DUP	aspy: 2-50% gouge (clay) w/ qtz pieces	VA05047825	0.56	
				45	50	0.5	2			2.0			50.0									B292603	104.19	105.16	0.108		aspy: 2-50%	VA05047825	0.97	
													20.0									B292604	105.16	106.68	0.104		v. broken; aspy: tr. to 20%	VA05047825	1.52	0.455
9	1	0.5	6.25	50	55	1.0	1				2.0		50.0									B292605	106.68	108.20	0.116		aspy: 2-50%	VA05047825	1.52	0.499
6	1	0.5	2.75	50		0.5	1						10.0									B292606	108.20	109.73	0.147		aspy: 1-10%	VA05047825	1.53	0.479
10	1	0.75	5.5	50	55	0.25							3.0									B292607	109.73	111.25	0.077		aspy: tr. - 3%	VA05047825	1.52	0.686
9	1	0.75	4.75	50		0.25	1			0.1			30.0									B292608	111.25	112.78	0.07		aspy: tr. - 30%	VA05047825	1.53	0.681
9	1	0.75	4.75	50		0.25	1			0.1			30.0									B292609	111.25	112.78	0.087	PD/CA		VA05047825	1.53	
																						B292610	STANDARD 5E		1.47	5E		VA05047825		
6	1	0.75	3.0	50	55								50.0									B292611	112.78	113.41	0.099		aspy: tr. - 50%	VA05047825	0.63	0.712
1	4	1.5	1.5	30									0.1									B292612	113.41	113.69	0.141			VA05047825	0.28	
1	6	0.25	0.25	45									80.0																	
						0.2	1						5.0									B292613	113.69	114.30	0.058		aspy: tr. - 5%	VA05047825	0.61	
2	1	0.5	1.0			0.2	1			0.1			3.0									B292614	114.30	115.82	0.037		aspy: tr - 3%; 2 veins plus broken pieces	VA05047825	1.52	0.578
9	1	0.5	3.25	35	50	0.1	1						50.0									B292615	115.82	117.35	0.043		aspy: tr. - 50%	VA05047825	1.53	0.393
																						B292616	BLANK		<0.005			VA05047825		
8	1	0.5	3.5	35	50	0.2	1						80.0									B292617	117.35	118.87	0.062		aspy: tr. - 80%	VA05047825	1.52	0.477
				50		0.5	1						3.0									B292618	118.87	120.40	0.093			VA05047825	1.53	0.59
4	1	0.25	2.0	40	60	0.5	1						10.0									B292619	120.40	121.92	0.126		aspy: tr. - 10%	VA05047825	1.52	0.295
10	1	0.5	5.25	45	50	0.5	1						30.0									B292620	121.92	123.44	0.121		aspy: tr. - 30%	VA05047825	1.52	0.358
2	1	0.5	1.0	40	55								3.0									B292621	123.44	124.97	0.047		aspy: tr - 3%	VA05047825	1.53	0.338
2	1	0.5	1.0	40	55								3.0									B292622	123.44	124.97	0.044	DUP		VA05047825	1.53	0.406
													0.1									B292623	124.97	126.49	0.051		bleached/ broken core	VA05047825	1.52	
1	1	1.0	1.0	55									0.1									B292624	126.49	128.02	0.117			VA05047825	1.53	
																						B292625	128.02	129.54	0.137		bleached out	VA05047825	1.52	0.434
6	1	0.5	4.75	50	60								1.0									B292626	129.54	131.06	0.158			VA05047825	1.52	0.335
2	1	0.5	1.0	60	65	0.1	1						5.0									B292627	131.06	132.59	0.229			VA05047825	1.53	0.336
17	1	1.5	9.0	55	60	0.1	1						3.0									B292628	132.59	134.11	0.214			VA05047825	1.52	0.271
17	1	1.5	9.0	55	60	0.1	1						3.0									B292629	132.59	134.11	0.228	PD/CA		VA05047825	1.52	
																						B292630	STANDARD 2B		3.26	2B		VA05047825		
11	1	1.0	6.25	40	60								90.0									B292631	134.11	135.64	0.221		aspy: 0-90% depending on vein	VA05047825	1.53	0.384
1	1	0.25	0.25	20							0.1											B292632	135.64	137.16	0.152			VA05047825	1.52	0.238
18	1	1.5	10.75	50						1.0			1.0																	
4	1	1.0		50	55								1.0									B292633	137.16	137.63	0.386			VA05047825	0.47	0.339
1	1	0.5	0.5	50									50.0									B292634	137.63	138.68	0.167			VA05047825	1.05	
4	6	0.5	2.0	60						40.0																				
2	1			50																		B292635	138.68	139.05	0.068			VA05047825	0.37	0.256
																						B292636	BLANK		<0.005			VA05047825		
																						B292637	139.05	139.80	0.106			VA05047825	0.75	
2	1	1.0	1.5	50						2.0						0.1						B292638	139.80	140.33	1.03			VA05047825	0.53	
1	4	1.75	1.75	55									0.1																	
3	6	10.0	14.0	50	55					85.0			15.0									B292639	140.33	140.60	0.287			VA05047825	0.27	0.484
5	1	0.5	3.0	50	60								1.0									B292640	140.60	141.73	0.065			VA05047825	1.13	
10	1	1.5	7.0	50	60	0.5	2			15.0			10.0									B292641	141.73	143.26	0.232			VA05047825	1.53	0.257
10	1	1.5	7.0	50	60	0.5	2			15.0			10.0									B292642	141.73	143.26	0.377	DUP		VA05047825	1.53	
8	1	0.5	5.25	50	55	2.0	2			0.1			1.0									B292643	143.26	144.27	0.095			VA05047825	1.01	0.294
3	1	0.25	0.75	55	40					0.1			0.1									B292644	144.27	144.78	0.265			VA05047825	0.51	NSS

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2005 PAGE 7 of 10		
DRILL HOLE # : DG05-280C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; QND = 10; QND (fg) = 11; QNDD (dyke) = 12; QMON = 20; DIOR = 25; MQD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		144.54	158.50							
10		158.50	162.04	Bleached/alt'd zone. Core is light green to light grey-white. Carbs are spotted w/in core like 'olive loaf'. Carb vns & stringer are present. sheeted vning continues, vns are ranging from 0.25-1.5cm thick and angle to CA has increased to ~70-75° to CA.		4	3	1	2	
10		162.04	163.65							
10		163.65	164.12	Sulphide qtz vn contacts @~65-70° to CA. 20-25% py & 20-25% aspy, sulphides are dissem throughout, but are somewhat oriented ~70° to CA (see photo). Surrounding core is alt'd to sericite/chlorite, yet coherent core.		2	2	1	1	
10		164.12	164.55							
10		164.55	165.03	Qtz sulphide vn w/ 2% aspy & ~2% py. Sulphide vnlets in vn are @~60-70° to CA.						
10		165.03	168.42	At 167.52m a slickenside @20° to CA, aspy on surface sheared & partially oxidized.						
10		168.42	168.64	Qtz/carb semi-massive py/aspy vn @~65-70° to CA. Alt'd selvage is continuous to 169.55m. Alt'n is abundant w/ sericite, minor chlorite (5%), little to no mafics, core is bleach & scratchable w/ a nail. Sheeted vning continues w/ spacing of vns/vnlets @~2-5cm apart w/in selvage.	1	3	2		2	
10		168.64	170.06							
10		170.06	170.69	Highly alt'd selvage leading to fault gouge clay @170.69-170.76m. Selvage is sericite abundant (25-30%), chlorite is ~5-8%. No mafics visible, minor relict qtz vns highlighted by aspy disserns or stringer @ typical 60-70° to CA.		4	2		2	
10		170.76	172.21	Core is mod alt'd, little to no mafics, essentially all selvage.		4	2	1	2	
10		172.21	172.49							
10		172.49	174.71	Core is mod alt, little to no mafics, essentially all selvage.		4	2	1	2	
10		174.71	175.26							
10		175.26	175.43	Core is extremely bleached & etched yet v. coherent (looks sand blasted & acidified). Stringers of py & aspy run w/ some minor direction ~70-80° to CA. Sericite & chlorite present.		3	2	2	1	
10		175.43	177.60							
10		177.60	177.64	A 4cm wide qtz/aspy (15%) vn @80° to CA. Alt'd selvage large & alt'n is significant.	1	4	2			
10		177.64	178.56							
10		178.56	181.36	Sheeted vning continues @70-80° to CA w/ spacing ~@5-8cm at most. From 181.36-182.66m, core is too alt'd to see vning system, yet continues from next box over.						
10		181.36	184.24							
10		184.24	185.93	Alt'd selvage that appears to be focused from a qtz/carb vn that's 6cm wide @45° to CA w/ 5-8% py & 3-5% aspy. @~185.29-185.93m. Alt'n intensifies to a category 4-5. Core is v. bleached, mafic free, w/ only sulphide stringers of ox'd py & aspy w/ abundant sericite & less chlorite. Dissems w/ GND perhaps not related to vning may be occurring but not observable enough to conclude for certain.		4	2	1	3	
10		185.93	190.50							
10		190.50	197.62	Sulphides, predominantly aspy, is being deposited via vnlets & stringers <0.1cm or mm sizes of qtz & carbs x-cutting larger vns, etc. Core would be estimated to contain ~2-3% sulphides total as a result. Sheeted vns appear to have disappeared but perhaps they haven't but the alt'n relicted the vns & discerning vns is no longer possible.		2	2		1	

DRILL LOG LEGEND P2

Date: June 6 - 10, 2005

PAGE 8 of 10

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages			% of VEIN & DISSEMINATED MATERIAL									Oxidation				Sample Number	Interval		Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5 (0-5)	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
1	6	1.5	1.5	40					55.0			35.0		2.0															
									0.1			5.0									B292645	144.78	146.30	0.14		x-cutting carb stringers	VA05047825	1.52	
5	1	1.0	5.5	40	70				0.1			30.0									B292646	146.30	147.83	0.152		aspy: tr to 30%, depending on vein	VA05047825	1.53	0.287
15	1	1.0	6.0	70	60	27	2		2.0			20.0									B292647	147.83	149.35	0.103		aspy: tr. To 20%, depending on vein	VA05047825	1.52	0.343
6	1	0.5	5.5	60	70	61.0	3					40.0									B292648	149.35	150.88	0.108		aspy: trace to 40%, depending on vein	VA05047825	1.53	0.308
6	1	0.5	5.5	60	70	61.0	3					40.0									B292649	149.35	150.88	0.104	PD/CA		VA05047825	1.53	
																					B292650	STANDARD 6F		2.48	6F		VA05047825		
15	1	0.5	9.0	65	70	2.0	2					5.0									B292651	150.88	152.40	0.122			VA05047825	1.52	0.319
16	1	0.5	6.5	65	70	0.2															B292652	152.40	153.92	0.041			VA05047825	1.52	
11	1	2.0	7.0	65	70	17.0	4	2	1.5			20.0									B292653	153.92	155.45	0.062		aspy: tr. To 20%, depending on vein	VA05047825	1.53	
7	1	0.75	2.75	50	70	27	3	2				5.0									B292654	155.45	156.97	0.123			VA05047825	1.52	
8	1	0.5	5.5	70								10.0									B292655	156.97	158.50	0.094		aspy: tr. To 10%, depending on vein	VA05047825	1.53	
																					B292656	BLANK		<0.005			VA05047825		
5	1	0.5	3.75	70	60	150	4	1				10.0									B292657	158.50	160.02	0.162		aspy: tr. To 10%, depending on vein	VA05047825	1.52	
8	1	2.75	7.5	60	70	150	3	1													B292658	160.02	161.54	0.318			VA05047825	1.52	
2	4	2.0	3.0	70					0.1			1.0																	
1	6	0.5	0.5	65					70.0			20.0																	
14	1	1.5	10.25	70	80	20	3					2.0									B292659	161.54	163.07	0.131			VA05047825	1.53	
7	1	3.0	6.0	70		33	3	1	2.0			10.0									B292660	163.07	163.70	1.17		aspy: tr. To 10%, depending on vein	VA05047825	0.63	
1	6	35.75	35.75	65	70	43	4		25.0			25.0									B292661	163.70	164.12	0.529			VA05047825	0.42	
1	6	35.75	35.75	65	70	43	4		25.0			25.0									B292662	163.70	164.12	0.615	DUP		VA05047825	0.42	
2	1	1.5	2.0	70								30.0									B292663	164.12	164.59	0.866		aspy: tr. To 30%, depending on vein	VA05047825	0.47	
1	1	42.0	42.0	70		78	4	2	2.0			3.0									B292664	164.59	165.03	0.78			VA05047825	0.44	
5	1	0.5	3.5	75	80				25.0			25.0									B292665	165.03	166.12	0.167			VA05047825	1.09	
9	1	5.0	11.5	70	75	23	3	1	2.0			10.0									B292666	166.12	167.64	0.458			VA05047825	1.52	
6	1	1.25	5.0	70					1.0			2.0									B292667	167.64	168.42	0.341			VA05047825	0.78	
1	3	12.0	12.0	60	70	150	4	1	25.0			10.0		8.0		8.0					B292668	168.42	168.64	1.36		other is carb	VA05047825	0.22	
1	6	3.25	3.25	65	70	150	4	1	100.0																				
1	3	12.0	12.0	60	70	150	4	1	25.0			10.0		8.0		8.0					B292669	168.42	168.64	1.38	PD/CA		VA05047825	0.22	
1	6	3.25	3.25	65	70	150	4	1	100.0																				
																					B292670	STANDARD 7G		4.57	7G		VA05047825		
2	1	0.5	1.0	65								1.0									B292671	168.64	169.16	0.207			VA05047825	0.52	
17	1	1.0	7.25	75	80	150	3		0.1			15.0									B292672	169.16	170.69	0.186		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
17	1	1.0	10.5	70	75	150	3					15.0									B292673	170.69	172.21	0.22		aspy: tr. To 15%, depending on vein	VA05047825	1.52	
13	1	1.5	8.0	70	75	120	3		0.1			15.0									B292674	172.21	173.74	0.219		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
10	1	1.0	6.25	60	70	150	3		0.1			1.0									B292675	173.74	175.26	0.212			VA05047825	1.52	
																					B292676	BLANK		<0.005			VA05047825		
7	1	1.25	4.75	75	80	150	3	2	20.0			25.0									B292677	175.26	176.25	0.157		py: tr. To 20%, depending on vein aspy: tr to 30%, depending on vein	VA05047825	0.99	
13	1	0.5	6.0	70		0.1	1					0.1									B292678	176.25	176.78	0.114			VA05047825	0.53	
26	1	4.25	17.0	75	80	32	2		0.1			15.0									B292679	176.78	178.31	0.24		aspy: tr. To 15%, depending on vein	VA05047825	1.53	
14	1	0.5	8.75	65	80							3.0									B292680	178.31	179.67	0.099		aspy: tr. To 3%	VA05047825	1.36	
14	1	0.25	6.25	65	70				1.0			5.0									B292681	179.67	180.22	0.124		aspy: tr. To 5%, depending on vein	VA05047825	0.55	
1	4	1.5	1.5	65	70																								
14	1	0.25	6.25	65	70				1.0			5.0									B292682	179.67	180.22	0.173	DUP		VA05047825	0.55	
1	4	1.5	1.5	65	70																								
7	1	0.5	5.25	70	80							2.0									B292683	180.22	181.26	0.146			VA05047825	1.04	
5	1	0.5	2.75	65	70	74	5					5.0									B292684	181.26	182.12	0.103		aspy: tr. To 5%, depending on vein	VA05047825	0.86	
2	1	0.25	0.5	70								0.1									B292685	182.12	182.58	0.071			VA05047825	0.46	
1	4	0.75	0.75	70		42	5					2.0																	
25	1	1.0	8.0	60	70							0.1									B292686	182.58	184.24	0.081			VA05047825	1.66	
3	4	6.0	8.0	45	75	162	4		8.0			5.0		1.0							B292687	184.24	185.93	0.761		aspy: tr. To 5%, depending on vein	VA05047825	1.69	
				60	65				1.0			5.0									B292688	185.93	187.45	0.14		aspy: tr. To 5%, depending on vein too altered to see	VA05047825	1.52	
				60	65				1.0			5.0									B292689	185.93	187.45	0.127	PD/CA		VA05047825	1.52	
																					B292690	STANDARD 4D		0.461	4D		VA05047825		
10	1	0.5	5.25	75	80							0.1									B292691	187.45	188.98	0.023			VA05047825	1.53	
1	4	1.0	1.0	50								0.1																	
																					B292692	188.98	189.86	0.04		too alt'd to see	VA05047825	0.88	
2	1	1.5	2.0	70	75							0.1									B292693	189.86	190.60	0.03			VA05047825	0.74	

DRILL LOG LEGEND P1	DATE: June 6 - 10, 2006 PAGE 9 of 10	
DRILL HOLE # : DG05-280C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				At 195.58, the core becomes extremely alt'd to sericite & chlorite. The core is mafic-devoid & sulphides are ox'd almost completely. Some carb vnlets are preserved. Qtz eyes are small yet give core texture. Core almost is pure white in places yet core is competent, not clay. Appears as core has undergone acid etching from hot hydrofluids. At 195.95m a slickenside @ 40° to CA w/ a black graphitic looking ox'n product forming a thick coating (1-2mm) w/ slickensides on it		4	2		1	
10		197.62	198.35	The core is riddled w/ sulphide vnlets of py/aspy & ox'd sulphides. There is an abundance concentrated from 197.86-198.20m @~50% sulphides, ox'n is either high causing thick black graphite-like build up or it bismuthinite (unsure). Sulphides has relative angle of orientation @~40-55° to CA (see photos).						
10		198.35	202.78	Core becomes v. salt and pepper bleached w/ stringers & vnlets of predominantly aspy or ox'd grey sulphides throughout. Typical angle on discernable vns/vnlets @60-70°. To end of hole continued w/ unalt'd GND w/ fracs typical @60-85° to CA w/ some fracs occurring on vnlets of sulphides.		1	0	0	2	
10		202.78	206.65							
				EOH						

DRILL LOG LEGEND P2

Date: June 6 - 10, 2005

PAGE 10 of 10

LOGGED BY: Kristian Whitehead, Terry Croteau

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, ab = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides									Oxidation					Sample Number			Au (g/T)	sample type	vein comments	CSV	Width (m)	VA05047184 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other		From	To						
1	4	4.0	4.0	55	60	71.0	3			0.1																					
8	1	1.0	5.75	70		38	4		2				15.0									B292694	190.60	192.02	0.079			VA05047825	1.42	
13	1	0.75	5.75	45	60	150	2		1													B292695	192.02	193.55	0.073			VA05047825	1.53	0.351
																						B292696	BLANK		<0.006			VA05047825		
													10.0									B292697	193.55	195.07	0.038		none visible due to alt'n	VA05047825	1.52	0.228
																						B292698	195.07	196.50	0.143			VA05047825	1.43	0.35
																						B292699	196.50	197.62	0.078			VA05047825	1.12	0.286
																						B292700	197.62	198.35	1.165			VA05047825	0.73	
																						B292701	198.35	199.64	0.066			VA05047825	1.29	0.295
																						B292702	198.35	199.64	0.047	DUP		VA05047825	1.29	
1	4	0.5	0.5	50									0.1									B292703	199.64	201.17	0.066			VA05047825	1.53	0.264
1	6	0.5	0.5	80									20.0					5.0				B292704	201.17	202.69	0.061			VA05047825	1.52	0.273
3	1	1.0	2.5	65						0.1			3.0									B292705	202.69	204.22	0.118		aspy: tr. To 5%, depending on vein	VA05047825	1.53	0.325
7	1	0.5	4.0			6.0							20.0					4.0				B292706	204.22	205.74	0.049		aspy: tr. To 20%, depending on vein	VA05047825	1.52	0.343
																						B292707	205.74	206.65	0.022			VA05047825	0.91	
																						EOH								

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-281C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1001m

BEARING: 000 | DIP: -50°

DATE STARTED: June 8, 2005 (night) | DATE COMPLETED: June 11 (day)

COORD SYSTEM: NAD 27: EASTING: 459631 NORTHING: 7099239

COORD SYSTEM: NAD 83: EASTING: 459512 NORTHING: 7099424

NAD 27 (CORRECTED for historic grid): EASTING: 459601 NORTHING: 7099249

SECTION LINE(historic grid): 459601E

LOGGED BY: M. Stone

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: to 24.38m

Deviation:

Casing: 24.38m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
24.38	43.65	MSED
43.65	222.5	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B291824 - B292033

Requisition #: MASP448STRGOL.05Q | Date Shipped: 14-June-05

Lab Record #: VA05049846 | Date Received: 24-June-05

Duplicates:	B291842, B291861, BB291883, B291902, B291922, B291942, B291962, B291981, B292002, B292022
Preparation Duplicate/ Check Assay:	B291829, B291850, B291869, B291889, B291909, B291929, B291949, B291969, B291989, B292009, B292029
Standards:	B291830, B291850, B291870, B291890, B291910, B291930, B291950, B291970, B291990, B292010, B292030
Blanks:	B291836, B291856, B291876, B291716, B291936, B291956, B291970, B291990, B292016,

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	335.9	48	001.9	002.9
150	338.1	48.2	004.1	005.1
222.5	337	47.4	003	004

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: 8 to 11-June-05	PAGE	of 14	
DRILL HOLE #: DG05-281C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered		**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-24.38	0.00	24.38	Casing						
80	24.38-43.65	24.38	25.91	10cm GND section (24.38-24.48m); followed by metaseds w/ v. finely-laminated (<1mm) bedding, well-preserved w/ subtle compositional variation (i.e. more mafic/more felsic) btwn layers. Pure qtz pebbles make up 20% of total pebbles, have metaseds on margins so veining exists w/in metaseds. Ox'n through whole core.	3			1		
80		25.91	27.73	Metaseds as described above. One qtz vein offset by microfracture. Microfrac has same strike as bedding but cuts across w/in core. Strike 40° to CA.	2		1	1		
80		27.73	32.22	Gouge. Gravel to clay texture. V. few relicts of metaseds, pieces up to 6cm (qtz eyes or coherent mafic beds). Purple hue to some sections - high hematite content. Other zones have euhedral hematite grains ~2mm diameter. Color light yellowish brown w/ lenses ~1cm wide of pale whitish blue, dark brown, mustard yellow.	4	1		4		
80		32.22	33.74	Back to competent, moderately oxidized argillite as described above. Bedding @ 30° to CA. Beds have been moved along micro-fractures.	3	1		1		
80		33.74	36.45	Gouge as above (27.73-32.22m). Remnant hematitic bedding @ 34.4m, @ 25° to CA. Hematite crystals w/in qtz vns (2%).	4	1		4		
80		36.45	37.50	Gouge w/ qtz section 15cm wide.	3	1		3		
80		37.50	39.62	Clay to sandy-textured alt'd metaseds, 20% pebbles 1cm-4cm.	4	1		4		
80		39.62	43.65	GND infiltrates metaseds in 40cm, 30cm & 10cm sections. Carb (calcite) on frac faces.	3	1		1	1	
10	43.65-222.50	43.65	44.20	Unalt'd GND w/ carb/qtz veins & qtz veins w/ ~1cm selvages.	1				1	
10		44.20	45.62	Unalt'd GND except on fractures & micro-fractures where limonite is, and around qtz vns w/ tiny selvages.	1				1	
10		45.62	47.14	Calc & lim throughout GND veinlets & matrix. Crumbly texture.	2			1	2	
10		47.14	49.29	More competent GND w/ lim & calcite on fractures	1				1	
10		49.29	53.34	Crumbly GND w/ lim on micro-fractures & through matrix.	3	1		2	2	
10		53.34	54.86	8cm competent GND & gouge material in 10cm length.	3			2	2	
10		54.86	57.60	Competent but crumbly core, lim & calcite pervasive.	3			1	2	
10		57.60	61.34	1mm-2mm thick encrustations of lim on frac surfaces; calcite inside that layer, and through cracks in qtz vns.	2		1		1	
10		61.34	62.66	22cm gouge zone surrounded by 50cm selvage of alt'd GND. Color of alt'd material (selvage) is light brown. Gouge is whitish orange w/ pale blue/white clayey material w/ gravel-size qtz eyes/oxidized GND.	3	2	1	3	1	
10		62.66	64.01	Limonite stained, v. broken GND.	2	2	1	1	1	
10		64.01	65.53	Mod'ly alt'd GND. Few unalt'd sections (5cm long); rest pervaded w/ limonite.						
10		65.53	66.14	Minor alt'd GND. Ox'd selvages around qtz vns; calcite 1mm vnlets w/in veins & GND.	1	1	1		1	
10		66.14	67.06	Highly alt'd GND, limonite throughout matrix & veinlets. Color is pale greenish-yellowish brown & texture is clay to gravel. Common veinlet direction 10° to CA.	2	2	1	1	1	
10		67.06	67.47	Gouge to clay to sand texture. Slickensides defined in limonite/calcite fracture @ 25° to CA.	3	2	2	2	1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To							
2	1	4.0	4.5			0.4	q	2	2													B291824	24.38	25.91	0.020		qtz pieces	VA05049846	1.53	1.3	
8	1	3.0	11	35	20	0.5	q	2	2													B291825	25.91	27.43	0.009			VA05049846	1.52	5.3	0.277
2	1	0.5	1.0	15		0.5	q	2	1	2.0								5.0				B291826	27.43	27.73	0.026			VA05049846	0.30	6.7	0.174
2	1	0.3	0.6	15		1.0	q	2	2													B291827	27.73	28.96	0.089			VA05049846	1.23	1.6	
																						B291828	28.96	30.48	0.016			VA05049846	1.52	0.0	0.062
																						B291829	28.96	30.48	0.017	PD/CA		VA05049846	1.52	0.0	
																						B291830	STANDARD 5E		1.265	5E		VA05049846			
																						B291831	30.48	31.10	0.132			VA05049846	0.62	0.0	0.245
																						B291832	31.10	32.22	0.087			VA05049846	1.12	0.0	
3	1	1.8	2.4	50	55	6.0	q	1	2													B291833	32.22	33.74	0.013			VA05049846	1.52	2.0	0.326
																						B291834	33.74	35.06	0.032			VA05049846	1.32	0.0	NSS
2	1	1.0	2.0							2.0								5.0				B291835	35.06	36.58	1.020		qtz pc's, selvage gouged	VA05049846	1.52	1.3	0.13
																						B291836	BLANK		<0.005			VA05049846			
3	1	15	17	80																		B291837	36.58	37.50	0.062			VA05049846	0.92	3.3	0.486
																						B291838	37.50	38.13	0.585			VA05049846	0.63	0.0	
																						B291839	38.13	39.62	0.294			VA05049846	1.49	0.0	0.556
																						B291840	39.62	40.90	0.463			VA05049846	1.28	0.0	0.918
																						B291841	40.90	41.80	1.245			VA05049846	0.90	0.0	0.96
																						B291842	40.90	41.80	0.767	DUP		VA05049846	0.90	0.0	
2	1	1.2	2.4	80		4.0	q	3	1	2.0								5.0				B291843	41.80	43.65	0.383			VA05049846	1.85	1.1	0.769
8	3	0.5	2.0	80		1.0	q	3	3													B291844	43.65	44.20	0.099			VA05049846	0.55	14.5	
							cb	1																							
1	1	1.0	1.0	80		1.0	q	2	1												1.0						other' is hematite				
4	1	1.0	4.0	70		0.5	q				7.0											B291845	44.20	45.62	0.164			VA05049846	1.42	2.8	0.743
1	1	1.0	1.0	70		2.0	q	3													1.0	B291846	45.62	47.14	0.546		other' is hematite	VA05049846	1.52	0.7	1.59
							chl	3																							
																						B291847	47.14	47.87	0.086			VA05049846	0.73	0.0	0.46
																						B291848	47.87	48.43	0.063			VA05049846	0.56	0.0	0.936
																						B291849	47.87	48.43	0.089	PD/CA		VA05049846	0.56	0.0	
																						B291850	STANDARD 6F		2.680	6F		VA05049846			
																						B291851	48.43	49.29	0.724			VA05049846	0.86	0.0	
																						B291852	49.29	50.29	0.180			VA05049846	1.00	0.0	
																						B291853	50.29	51.82	0.332			VA05049846	1.53	0.0	2.27
																						B291854	51.82	53.34	0.150			VA05049846	1.52	0.0	1.32
																						B291855	53.34	54.50	0.598			VA05049846	1.16	0.0	1.045
																						B291856	BLANK		<0.005			VA05049846			
																						B291857	54.50	54.86	0.153			VA05049846	0.36	0.0	
																						B291858	54.86	56.19	0.360			VA05049846	1.33	0.0	1.06
2	1	1.0	1.5	60		2.0	q	3	2													B291859	56.19	57.60	0.911			VA05049846	1.41	1.4	0.934
							chl	1																							
4	1	1.0	2.5	65	60	2.0	q	3	1												1.0	B291860	57.60	59.27	0.179		other' is hematite	VA05049846	1.67	2.4	1.1
							s	1																							
4	1	4.0	12	60		2.0	q						5.0								1.0	B291861	59.27	60.76	4.050		other' is hematite	VA05049846	1.49	2.7	5.65
4	1	4.0	12	60		2.0	q						5.0								1.0	B291862	59.27	60.76	0.814	DUP		VA05049846	1.49	2.7	
2	1	0.6	1.2	60		0.5	q	1	2													B291863	60.76	61.34	0.870			VA05049846	0.58	3.4	1.48
							chl	1																							
																						B291864	61.34	62.66	0.386			VA05049846	1.32	0.0	
1	1	1.0	1.0	60		1.0	q	3	1													B291865	62.66	64.01	0.186			VA05049846	1.35	0.7	0.642
							chl	1																							
							s	2																							
3	1	2.0	5.0	50	60	3.0	q	1		0.1			4.0					5.0	4.0			B291866	64.01	65.53	0.350			VA05049846	1.52	2.0	2.48
							chl	1																							
							s	2																							
3	1	1.0	3.0																			B291867	65.53	66.14	0.438			VA05049846	0.61	4.9	0.805
																						B291868	66.14	67.06	0.156			VA05049846	0.92	0.0	
																						B291869	66.14	67.06	0.226	PD/CA		VA05049846	0.92	0.0	
																						B291870	STANDARD 6F		2.750	6F		VA05049846			
1	1	1.0	1.0	35		0.5	q	3	2													B291871	67.06	67.47	1.040			VA05049846	0.41	2.4	0.628
							chl	1																							

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION — Comments:	ROCK (Alteration) — Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		67.47	69.03	Limonite 90% pervasive in section, 10% unalt'd GND. Randomly-oriented calcite veinlets throughout.	3	2	2	1	1	
10		69.03	69.41	GND stained brown w/ little original texture remaining.	3	2	1	1	1	
10		69.41	70.31	Unalt'd GND & vns of qtz w/ moderate selvages. Lim & carb in less frequent veinlets.	1	1	1		1	
10		70.31	70.65	Limonite and carbonate staining pervasive. Overall, colour is light brown. 40% clay weathering makes rock weak but competent except 4cm gouge (clay)	3	3	1	2	1	
10		70.65	72.11	Limonite and carb less prevalent, but seen on ragged veinlets, generally trending ~10° to CA. Unaltered GND where not affected by sheeted vein set: 50% veins broken up (just linear qtz chunks)	1	1			1	
10		72.11	73.60	Limonite and carbonate pervading GND to weaker, but coherent core as at 70.31-72.11m. Early in sample, low angle fracture face shows lineated calcite (drawn - 40° to CA)	3	3	1	1	2	
10		73.60	74.46	Very weak rock due to pervasive limonite and calcite in < 0.2cm widths	3	2	1	2	1	
10		74.46	75.56	Sample is ~35% massive qtz, probably broken up and compacted old veins. GND weakened by pervasive lim and calcite.	3	2			2	
10		75.56	76.65	V. crumbly and clay-rich GND altered through pervasive limonite and calcite	3	4	1	2	2	
10		76.65	78.07	Sand-size material to GND chunks up to ~5cm.	4	3	1	2	1	
10		78.07	79.25	Extremely altered to white/brown clay-rich matrix. Calcite notable throughout.	3	3	1	1	2	
10		79.25	83.82	Gouge to crumbly, sericitized GND. Slickenside in muddy black clay on fract @10° to CA.	4	4	2	3	2	
10		83.82	84.60	Competent unaltered to moderate altered GND	1	2	1		1	
10		84.60	85.96	Old qtz/carb veins(@55°) overprinted by veinlets of limonite and calcite to 10°/110°. Veinlets have 2mm selvages. Very broken core, poor recovery here as well	2	2	1		2	
10		85.96	86.16	Sand. Pure. Medium brown	2					
10		86.16	87.51	Same as 85.60-85.96m, but more frequent carb/qtz veins. Lim covers fracture faces, at regular angles of 50/140°	1	1	1		1	
10		87.51	88.08	Unaltered GND w/ qtz veins and few lim veinlets. Ragged orientations, lim on straight fract too	1	1	1		1	
10		88.08	88.49	Calcitic and silica alteration more prevalent. Low angle fracture (10° to CA) w/ slickensides of ser and chl	1	1	1		2	
10		88.49	89.92	Lim/calc veinlets (1mm) weaken rock to v. broken. Texture of GND appears silicified, crystalline	2	2			1	
10		89.92	91.44	Few preserved sections of unalterd GND. 80% limonite stained, so pervasively that GND texture is erased	3	3	2		1	
10		91.44	92.96	30% unaltered GND w/ >2cm qtz veins w/ wide selvages	2	3	1		1	
10		92.96	93.61	Coherent, unaltered GND to 93.5m, where GND is limonized and brown coloured	1	1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other		From	To							
																						B291872	67.47	69.03	0.427			VA05049846	1.56	0.0	0.262
2	1	2.0	2.5	60		2.0	q	2														B291873	69.03	69.41	0.313			VA05049846	0.38	5.3	
							s	3																							
6	1	2.0	5.0	60		2.0	q	3		8.0								4.0				B291874	69.41	70.31	0.286			VA05049846	0.90	6.7	
							s	3																							
							chl	1																							
0																						B291875	70.31	70.65	2.840			VA05049846	0.34	0.0	1.02
																						B291876	BLANK		<0.005			VA05049846			
8	1	2.0	10.0	45		5.0	q	2	1	0.1			0.1					5.0	5.0			B291877	70.65	72.11	0.696			VA05049846	1.46	5.5	4.05
							s	3																							
1	6	1.0	1.0	60		1.0	chl	2		5.0	15.0		10.0					4.0	4.0												
							q	2																							
4	1	1.2	2.8	60		2.0	q	1	2	3.0			2.0					4.0	4.0			B291878	72.11	73.60	0.956			VA05049846	1.49	2.7	
							s	4																							
2	1	1.0	2.0	90		10.0	q	4	4	3.0			2.0					4.0	4.0			B291879	73.60	74.46	0.829			VA05049846	0.86	2.3	
3	1	1.2	5.0	60						8.0			5.0					4.0				B291880	74.46	75.56	1.095		selvage indistinct	VA05049846	1.10	2.7	3.17
1	4	1.0	1.0			3.0	q	2	1				5.0						3.0												
							cb	2																							
							chl	1																							
0																						B291881	75.56	76.65	0.401			VA05049846	1.09	0.0	
0																						B291882	75.56	76.65	0.271	DUP		VA05049846	1.09	0.0	
1	1	0.8	0.8	75		2.0	q	3	4				0.1						5.0			B291883	76.65	78.07	0.847			VA05049846	1.42	0.7	1.85
							s	3																							
1	4	2.0	2.0	80		5.0	cb	3	4													B291884	78.07	79.25	0.296			VA05049846	1.18	0.8	1.925
							chl	1																							
0																						B291885	79.25	80.77	0.394			VA05049846	1.52	0.0	2.63
																						B291886	80.77	82.30	0.317			VA05049846	1.53	0.0	1.735
																						B291887	82.30	82.80	0.283			VA05049846	0.50	0.0	2.19
																						B291888	82.80	83.82	0.691			VA05049846	1.02	0.0	
																						B291889	82.80	83.82	0.532	PD/CA		VA05049846	1.02	0.0	
																						B291890	STANDARD 1A		0.930	1A		VA05049846			
7	3	0.3	2.1	55		2.0	q	2		2.0								2.0				B291891	83.82	84.60	0.246			VA05049846	0.78	9.0	2.84
							s	3																							
							chl	1																							
																						B291892	84.60	85.96	0.295			VA05049846	1.36	0.0	1.495
																						B291893	85.96	86.16	0.324			VA05049846	0.20	0.0	
11	3	2.0	4.5	80	65	1.0	q	1	1	1.0			1.0					4.0	4.0			B291894	86.16	87.51	0.218			VA05049846	1.35	8.1	1.625
							s	1																							
							chl	1																							
3	3	1.0	3.0	60		2.0	q	2	3		0.1		1.0						4.0			B291895	87.51	88.08	0.392			VA05049846	0.57	5.3	
							s	2																							
							chl	1																							
5	3	1.0	4.0	70	60	8.0	q	2	1				1.0						4.0			B291896	88.08	88.49	0.045		Missed Blank Stamp	VA05049846	0.41	12.2	0.974
							s	2																							
							chl	2																							
																						B291897	88.49	89.92	0.269			VA05049846	1.43	0.0	
3	1	1.0	3.0	55		15.0	q	3	3	20.0								2.0				B291898	89.92	91.44	0.294			VA05049846	1.52	2.0	0.717
							s	3																							
							chl	3																							
5	1	4.0	7.0	45		4.0	q	4		5.0			3.0					5.0				B291899	91.44	92.96	0.100			VA05049846	1.52	3.3	0.686
							s	3																							0.901
							chl	1																							
0																						B291900	92.96	93.61	0.038			VA05049846	0.65	0.0	0.634

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION — Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		93.61	94.49	Heavily broken and limonized GND. Calcite and chlorite on fracture faces w/ no lineation	2	2	1		1	
10		94.49	95.59	Unaltered GND except selvages, around qtz veins and 1-2mm around veinlets/fractures covered w/ limonite and calcite	1	1	1			
10		95.59	96.01	Limonized and broken GND; weak and crumbly grey qtz vein	2	2	1		1	
10		96.01	97.54	Unaltered GND except carb + lim veinlet/fract w/ 1-2mm selvage. Larger qtz veins have weak silica-defined selvage	1	1			1	
10		97.54	99.06	Extremely altered GND. Chlorite, sericite, limonite throughout (colourful - yellow, orange speckles, greenish greyish brown). Original GND texture completely overprinted by alteration. Carbonate throughout as well (yellow part)	3	4	3	2		
10		99.06	100.58	Unaltered GND w/ qtz and qtz/carb veins w/ selvages (increased chlorite)	2	1	2		1	
10		100.58	103.26	Unaltered GND w/ qtz and qtz/carb veins w/ selvages (increased chlorite)	2	1	2		1	
10		103.26	104.12	Limonized and silicified GND gouge (yellowish brown) to competent (yellowish grey). Gouge section from 104.0 - 104.2m.	2	3	3	2	2	
10		104.12	104.64	Mod. Altered GND. Low angle (near parallel to CA.) veinlets (1-2mm) covered in lim and calcite. Also in random orientations	1	1	1		1	
10		104.64	105.80	Alt'd GND. Lim pervasive through 90%, rest is silicified. One small lens of ox'd sulphides @ 105.7m, 1mm wide, 3cm long, black	3	3		4	2	
10		105.80	106.43	Pale bluish white clay altered w/ veinlets, limonized (random) Hematite oxidized in qtz vein colours it pink	1	4	1	4	1	
10		106.43	107.32	V. mafic GND (qtz preferentially dragged to vein?) Separated by lim/q/cb alteration around qtz veins	1	3	1		1	
10		107.32	108.20	Extremely alt'd GND, colourful, as at 97.54- 99.06m. Lim fractures parallel to CA. Ser and chl on fract to 25° to C.A. Lim staining for 10cm (pervasive)	3	3	3	2	2	
10		108.20	109.73	Unaltered GND separated by selvages around qtz and carb veins. One qtz vein offset on 1mm fracture. Sericite lineation on fract face (10° to CA).	2	2		1	2	
10		109.73	110.35	Mod'ly alt'd GND; selvages oxidized	2	2	1		2	
10		110.35	111.05	Extremely altered GND, pale bluish white. Carb appears pervasive, stemming from randomly oriented veinlets throughout	1	4	2	3	4	
10		111.05	112.13	Extremely altered GND stained black, soft, flakey mineral	1	4	2	3	2	
10		112.13	125.51	Chloritized, clay-altered GND w/ <20cm blackened sections. Only slight variation in composition throughout. Overall colour is pale bluish green, and either white or black. Soft, clay to crumbly texture. @120.40m, a lens of grey clay w/ lineation, drawn, face is at 50° to CA.	1	4	3	3	3	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL															Interval								
										Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
4	1	0.5	2.0	15		5.0	q	3	1				5.0						2.0			B291901	93.61	94.49	0.201			VA05049846	0.88	4.5	
							chl	2																							
							s	2																							
																						B291902	93.61	94.49	0.092			VA05049846	0.88	0.0	
3	1	1.5	3.5	35		5.0	q	1		0.1								5.0				B291903	94.49	95.59	0.144			VA05049846	1.10	2.7	0.941
							chl	1																							
							s	1																							
2	3	0.5	1.0	45		1.0	q	3										1.0				B291904	95.59	96.01	0.417			VA05049846	0.42	4.8	
							cb	3																							
1	1	1.0	1.0	70																											
6	1	3.0	9.0	55		1.0	q	1	1	2.0			0.1					5.0				B291905	96.01	97.54	0.172			VA05049846	1.53	3.9	0.533
6	1	1.0	5.0	70			q	4	3				5.0									B291906	97.54	99.06	0.295			VA05049846	1.52	3.9	1.35
							s	4																							
							ch	3																							
5	3	2.0	5.0	30		10.0	q	4					5.0						2.0			B291907	99.06	100.58	0.447			VA05049846	1.52	3.3	0.704
							cb	4																							
							chl	3																							
6	3	2.0	4.0	60	45	2.0	q	3	1	4.0			12.0					4.0				B291908	100.58	102.11	0.158			VA05049846	1.53	3.9	0.557
							cb	2																							
							s	1																							
6	3	2.0	4.0	60	45	2.0	q	3	1	4.0			12.0					4.0				B291909	100.58	102.11	0.182	PD/CA		VA05049846	1.53	3.9	
							cb	2																							
							s	1																							
																						B291910	STANDARD 7G		4.670	7G		VA05049846			
2	3	1.0	2.5	35	55	1.5	q	2	2	3.0			5.0					5.0	3.0			B291911	102.11	103.26	0.271			VA05049846	1.15	1.7	0.906
							s	1																							
							cb	2																							
0																						B291912	103.26	104.12	0.446			VA05049846	0.86	0.0	0.712
1	1	1.0	1.0	40		1.0	q	3	1	0.1			3.0					5.0	3.0			B291913	104.12	104.64	0.106			VA05049846	0.52	1.9	
3	3	1.0	3.0	60		20.0	q	1	3		0.1							2.0				B291914	104.64	105.80	0.169			VA05049846	1.16	2.6	
							lim	3																							
							s	2																							
							arg	4																							
1	1	1.5	1.5	45		10.0	arg	3	1		10.0										5.0	B291915	105.80	106.43	5.850		other' is hematite	VA05049846	0.63	1.6	0.981
							chl	1																							
							s	4																							
							cb	2																							
																						B291916	BLANK		<0.005			VA05049846			
5	1	1.0	5.0	45		1.0	q	2		10.0								3.0				B291917	106.43	107.32	0.430			VA05049846	0.89	5.6	1.035
2	4	0.5	1.0	15	115	0.1	cb	5																							
0																						B291918	107.32	108.20	1.535			VA05049846	0.88	0.0	
3	1	1.5	2.0	70	60	5.0	q	3	4	5.0			5.0					5.0				B291919	108.20	109.73	0.308			VA05049846	1.53	2.0	0.983
							s	3																							
5	3	1.0	4.0	70		15.0	cb	3	4																						
							arg	3																							
2	1	1.0	1.6	70		15.0	q	1	3													B291920	109.73	110.35	0.061			VA05049846	0.62	3.2	1.13
							s	5																							
0																						B291921	110.35	111.05	0.129			VA05049846	0.70	0.0	
0																						B291922	110.35	111.05	0.187	DUP		VA05049846	0.70	0.0	
3	1	1.0	2.0	70			s	4	1				3.0									B291923	111.05	112.13	0.297			VA05049846	1.08	2.8	0.78
							chl	3																							
							arg	3																							
							cb	3																							
0																						B291924	112.13	112.78	0.234			VA05049846	0.65	0.0	
1	1	1.0	1.0	50			s	5					0.1									B291925	112.78	114.30	0.832			VA05049846	1.52	0.7	0.652
							chl	4																							
							arg	4																							
							cb	4																							
3	1	1.5	3.0	50	80		s	5			0.1							3.0				B291926	114.30	115.02	0.440			VA05049846	0.72	4.2	0.602
							chl	4																							
							arg	4																							
							cb	4																							

DRILL LOG LEGEND P1 | DATE: 8 to 11-June-05 | PAGE 1 of 14

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION — Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.51	128.34	Clay to gravel texture. Colour is medium grey.	1	4	3	4	4	
10		128.34	129.43	Minor alt'd GND	1	2	1		1	
10		129.43	134.54	Unalt'd GND between sheeted qtz veins		1	1		1	
10		134.54	135.84	Sericitized GND zone. Central vein not visible. Zone begins/ends at ~45° to CA.		3	2		1	
10		135.84	145.19	Numerous qtz veins with ser/chl/cb altered selvages. Selvage dominates this section, to 90%.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL																						
										Sulphides										Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To								
0																						B291927	115.02	117.35	0.176			VA05049846	2.33	0.0	1.08
1	1	1.0	1.0	70			s	5														B291928	117.35	118.87	0.020			VA05049846	1.52	0.7	0.926
							chl	4																							
							arg	4																							
							cb	4																							
1	1	1.0	1.0	70			s	5														B291929	117.35	118.87	0.026	PD/CA		VA05049846	1.52	0.0	
							chl	4																							
							arg	4																							
							cb	4																							
																						B291930	STANDARD 4D		0.462	4D		VA05049846			
1	4	0.5	0.5	70			s	5														B291931	118.87	120.40	1.395			VA05049846	1.53	0.7	0.991
							chl	4																							
							arg	4																							
							cb	4																							
0																						B291932	120.40	121.16	0.268			VA05049846	0.76	0.0	0.742
0																						B291933	121.16	121.92	0.113			VA05049846	0.76	0.0	
2	1	2.0	3.0	80			s	5		10.0	2.0							4.0				B291934	121.92	123.44	1.415			VA05049846	1.52	1.3	1.245
							chl	4																							
							arg	4																							
							cb	4																							
1	6	0.5	0.5	70			s	5		20.0								4.0													
							chl	4																							
							arg	4																							
							cb	4																							
2	1	3.0	6.0	80			s	5		5.0	5.0							4.0				B291935	123.44	124.97	0.635			VA05049846	1.53	1.3	0.704
							chl	4																							
							arg	4																							
							cb	4																							
																						B291936	BLANK		<0.005			VA05049846			
																						B291937	124.97	125.51	0.172			VA05049846	0.54	0.0	1.155
0																						B291938	125.51	126.01	1.720			VA05049846	0.50	0.0	
0																						B291939	126.01	126.82	0.258			VA05049846	0.81	0.0	
0																						B291940	126.82	128.34	0.279			VA05049846	1.52	0.0	
2																						B291941	128.34	129.43	0.466			VA05049846	1.09	1.8	
																						B291942	128.34	129.43	1.155	DUP		VA05049846	1.09		
5	1	2.0	7.0	60		4.0	q	3	0		10.0		5.0					1.0	2.0			B291943	129.43	130.32	1.330			VA05049846	0.89	5.6	
							chl	2																							
							s	2																							
9	1	2.0	6.5	60		3.0	q	3	0		15.0	0.1	5.0					3.0	3.0			B291944	130.32	131.06	0.342			VA05049846	0.74	12.2	
							chl	2																							
							s	2																							
8	1	2.0	7.0	60		10.0	chl	3	0	5.0	8.0		3.0					3.0	3.0			B291945	131.06	132.59	0.309			VA05049846	1.53	5.2	
							s	3	0																							
							q	1																							
1	6	2.0	2.0	60		10.0	chl	3	0	5.0	30.0		10.0					4.0	2.0													
							s	3																							
							q	1																							
5	1	1.0	5.0	60		8.0	chl	3	0				10.0						3.0			B291946	132.59	134.11	1.040			VA05049846	1.52	3.3	
							s	2																							
1	1	1.0	1.0	65		0.0	q	3			3.0		2.0					1.0	3.0			B291947	134.11	134.54	0.033			VA05049846	0.43	2.3	
2	4	0.2	0.4	50		40.0	s	4			5.0		5.0					1.0	3.0			B291948	134.54	135.84	0.202			VA05049846	1.30	1.5	
							chl	2																							
							cb	2																							
2	4	0.2	0.4	50		40.0	s	4			5.0		5.0					1.0	3.0			B291949	134.54	135.84	0.163	PD/CA		VA05049846	1.30	0.0	
							chl	2																							
							cb	2																							
																						B291950	STANDARD 5E		1.525	5E		VA05049846			
3	1	3.5	6.0	50	65	4.0	s	4		5.0	5.0							3.0				B291951	135.84	136.84	0.242			VA05049846	1.00	3.0	
							chl	2																							
							cb	2																							
9	1	1.5	6.0	50		4.0	s	4		5.0	5.0		2.0					3.0	4.0			B291952	136.84	137.55	0.488			VA05049846	0.71	12.7	
							chl	2																							
							cb	2																							
6	1	2.0	7.0	45	70		s	4		2.0	2.0		1.0					3.0	0.0			B291953	137.50	138.68	0.396			VA05049846	1.18	5.1	
							chl	3																							
							cb	2																							
2	4	0.3	0.5	60			s	4		2.0	2.0		1.0					3.0	0.0													
							chl	3																							
							cb	2																							

DRILL LOG LEGEND P1	DATE: 8 to 11-June-05	PAGE 9 of 14	
DRILL HOLE #: DG05-281C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				From 141.92 to 142.07m is one 15cm qtz vein w/ 3 lenses of massive sulphides 1-5mm wide						
10		145.19	148.30	Unalt'd GND w/ qtz veins. Low angle veins have > sulphides		2	1		1	
10		148.30	150.88	Carb-rich GND. Fractures and matrix in-filled. Fractures trend to 40°/140°. Crumbly, weak texture.		3	3	1	3	
10		150.88	152.40	Unalt'd GND w/ qtz veins		2	1		1	
10		152.40	158.50	Carb-infused GND (as at 148.3-150.88m)		3	3	1	3	
				At 157.10-157.20m, gouge zone. Strong slickensides in sericite and ox'd pyrite on low-angle fracture.						
10		158.50	170.69	GND, unalt'd. Sheeted milky qtz veins		1	1		1	
				At 163.35: po/ser (50/50) zone 5x3cm.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

PAGE 10 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To								
3	1	3.0	5.0	25	40		s	4		2.0								5.0				B291954	138.68	140.99	0.177			VA05049846	2.31	1.3	
							chl	4																							
							cb	3																							
2	4	0.5	1.0	45			s	3		5.0	5.0							2.0													
							chl	3																							
							cb	3																							
7	1	3.0	10.0	55		40.0	s	3		5.0			2.0					3.0				B291955	140.99	141.92	1.105			VA05049846	0.93	7.5	
							chl	3																							
							cb	3																							
																						B291956	BLANK		<0.005			VA05049846			
1	1	15.0	15.0	45		35.0	s	3		10.0			2.0					4.0				B291957	141.92	142.09	0.107			VA05049846	0.17	5.9	
							chl	3																							
							cb	3																							
6	3	2.0	2.0	50	40	10.0	s	3		5.0			3.0					3.0				B291958	142.09	143.26	1.315			VA05049846	1.17	5.1	
							chl	3																							
							cb	3																							
6	1	5.0	12.0	60	70	40.0	s	3		10.0	15.0							4.0				B291959	143.26	144.78	0.238			VA05049846	1.52	3.9	
							chl	3																							
							cb	3																							
2	1	3.0	5.0	70		20.0	s	3		10.0								4.0				B291960	144.78	145.19	1.530			VA05049846	0.41	4.9	
							chl	3																							
							cb	3																							
6	1	1.0	6.0	60	45	4.0	s	2		5.0	8.0		5.0					4.0	3.0			B291961	145.19	146.30	0.596			VA05049846	1.11	5.4	
							chl	1																							
							cb	1																							
6	1	1.0	6.0	60	45	4.0	s	2		5.0	8.0		5.0					4.0	3.0			B291962	145.19	146.30	0.816	DUP		VA05049846	1.11	5.4	
							chl	1																							
							cb	1																							
8	1	1.0	6.0	55	35	2.0	q	4			10.0	0.1	1.0					1.0	3.0			B291963	146.30	147.83	0.639			VA05049846	1.53	5.2	
							cb	2																							
3	3	0.5	1.5	60	50	1.0	q	4		2.0	5.0	5.0						3.0				B291964	147.83	148.30	6.340			VA05049846	0.47	6.4	
							cb	2																							
3	1	3.0	5.0	65		0.0							5.0						3.0			B291965	148.30	149.35	1.545			VA05049846	1.05	2.9	
8	3	3.0	8.0	65		1.0	cb	1					1.0						4.0			B291966	149.35	150.88	0.711			VA05049846	1.53	5.2	
							q	2																							
							chl	1																							
8	1	2.0	5.0	30	50	1.0	cb	1			2.0		5.0						3.0			B291967	150.88	152.40	0.285			VA05049846	1.52	5.3	
							q	2																							
							chl	1																							
4	1	2.0	5.0	40		2.0	q	4	0		5.0		1.0						5.0			B291968	152.40	153.92	0.627			VA05049846	1.52	2.6	
							cb	2																							
4	1	2.0	5.0	40		2.0	q	4	0		5.0		1.0						5.0			B291969	152.40	153.92	0.875	PD/CA		VA05049846	1.52	2.6	
							cb	2																							
																						B291970	STANDARD 2B		3.140	2B		VA05049846			
2	4	3.0	5.0	30		0.0																B291971	153.92	155.45	0.388			VA05049846	1.53	1.3	
1	3	1.0	1.0	30		4.0	q	4	0	0.1																					
							chl	3	0																							
6	1	2.0	6.0	30	55	2.0	q	3	0		2.0							1.0				B291972	155.45	156.97	0.364			VA05049846	1.52	3.9	
							chl	3																							
2	1	3.0	4.0	50		2.0	q	1	0	1.0			10.0					3.0	3.0			B291973	156.97	158.50	0.170			VA05049846	1.53	1.3	
							s	2																							
							chl	2																							
7	1	1.2	5.5	50		2.0	q	3		3.0			5.0						5.0			B291974	158.50	160.02	0.099			VA05049846	1.52	4.6	
							s	1																							
							chl	1																							
9	1	1.0	4.0	50		1.0	q	3			5.0							1.0				B291975	160.02	161.54	0.241			VA05049846	1.52	5.9	
							s	1																							
							chl	1																							
																						B291976	BLANK		<0.005			VA05049846			
11	1	3.0	10.0	50		4.0	q	3			10.0							1.0				B291977	161.54	163.07	1.770			VA05049846	1.53	7.2	
							s	1																							
							chl	2																							
3	1	1.0	2.0	50		2.0	q	3			10.0							1.0				B291978	163.07	164.59	0.353			VA05049846	1.52	2.0	
							s	1																							
							chl	2																							

DRILL HOLE #: DG05-281C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		170.69	173.74	Carb-rich zone again. Crumbly GND.		1	2		2	
10		173.74	178.31	Unalt'd GND w/ milky white qtz veins		2	1		1	
10		178.31	181.36	Slightly more carb on microfractures and throughout, appears as veinlets in random orientations		2	1		2	
10		181.36	184.90	Minor silicified GND (qtz milky, boundaries gradational). Calcite on microfractures/irregular veinlets		1	1		1	
10		184.90	185.24	One qtz vein w/ big selvage		3	3			
10		185.24	189.53	Unalt'd GND. Chl section at 189.45m						
10		189.53	191.12	Shear zone. GND gains fabric (foliation) to 80°.	2	2	2	1	1	
10		191.12	192.55	Unalt'd GND w/ qtz veins		2	4		2	
10		192.55	194.40	Qtz and carb veins w/in heavily chloritized zone						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 6 = quartz/chlorite, 8 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To							
7	1	1.0	5.0	45		2.0	q	2			10.0							1.0				B291979	164.59	166.12	1.150			VA05049846	1.53	4.6	
							s	1																							
							chl	1																							
4	1	1.0	4.0	50		2.0	q	2			5.0											B291980	166.12	167.64	0.407			VA05049846	1.52	2.6	
							s	1																							
							chl	1																							
6	1	1.5	5.0	45		1.0	q	2			15.0		3.0									B291981	167.64	169.16	0.853			VA05049846	1.52	3.9	
							s	1																							
							chl	1																							
6	1	1.5	5.0	45		1.0	q	2			15.0		3.0									B291982	167.64	169.16	0.083	DUP		VA05049846	1.52	3.9	
							s	1																							
							chl	1																							
9	1	1.5	5.0	50		6.0	q	2		5.0	5.0		0.1					3.0	5.0			B291983	169.16	170.69	1.170			VA05049846	1.53	5.9	
							s	1																							
							chl	1																							
9	1	1.0	6.0	50		1.0	q	2		2.0	2.0							1.0				B291984	170.69	172.21	0.280			VA05049846	1.52	5.9	
							s	1																							
							chl	1																							
3	4	0.8	2.0	15		0.0				0.0																					
9	1	2.0	11.0	50		3.0	q	2			5.0		0.1						2.0			B291985	172.21	173.74	0.237			VA05049846	1.53	5.9	
							s	1																							
							chl	1																							
7	1	3.0	10.0	40		2.0	q	3	0		5.0		0.1						5.0			B291986	173.74	175.26	0.963			VA05049846	1.52	4.6	
							chl	2																							
							cb	1																							
7	1	4.0	9.0	50		1.0	q	3			5.0		1.0						4.0			B291987	175.26	176.78	0.176			VA05049846	1.52	4.6	
							chl	2																							
							cb	1																							
6	1	5.5	10.0	50	40	2.0	q	3			5.0		1.0						0.0			B291988	176.78	178.31	0.232			VA05049846	1.53	3.9	
							chl	2																							
							cb	1																							
6	1	5.5	10.0	50	40	2.0	q	3			5.0		1.0						0.0			B291989	176.78	178.31	0.254	PD/CA		VA05049846	1.53	0.0	
							chl	2																							
							cb	1																							
																						B291990	STANDARD 4D		0.453	4D		VA05049846			
7	1	1.2	7.2	70		2.0	q	3			5.0											B291991	178.31	179.83	1.810			VA05049846	1.52	4.6	
							s	3																							
3	1	2.0	2.0	50		2.0	q	3			5.0		3.0						4.0			B291992	179.83	181.36	0.237			VA05049846	1.53	2.0	
							s	3																							
							cb	2																							
5	1	1.0	5.0	50		2.0	q	3			5.0		1.0						4.0			B291993	181.36	182.88	0.069			VA05049846	1.52	3.3	
							s	3																							
							cb	2																							
																						B291994	182.88	184.40	0.037			VA05049846	1.52	0.0	
5	1	1.5	3.5	40		2.0	q	3		3.0			3.0						3.0			B291995	184.40	184.90	0.087			VA05049846	0.50	10.0	
							chl	1																							
																						B291996	BLANK		<0.005			VA05049846			
1	1	2.0	2.0	50		23.0	q	2		10.0			3.0					2.0	3.0			B291997	184.90	185.24	1.130			VA05049846	0.34	2.9	
							chl	4																							
2	1	1.0	2.0	50		0.2	q	2			5.0							1.0				B291998	185.24	185.93	0.044			VA05049846	0.69	2.9	
0																						B291999	185.93	187.45	0.024			VA05049846	1.52	0.0	
3	1	1.0	3.0	50		1.0	q	4	0	1.0			1.0					2.0	3.0			B292000	187.45	188.98	0.019			VA05049846	1.53	2.0	
							chl	2																							
							s	2																							
0																						B292001	188.98	189.53	0.022			VA05049846	0.55	0.0	
0																						B292002	188.98	189.53	0.020	DUP		VA05049846	0.55	0.0	
2	6	1.0	2.0	70		0.0				40.0								5.0				B292003	189.53	190.50	0.055			VA05049846	0.97	2.1	
4	6	1.0	3.0	70		0.0				40.0								5.0				B292004	190.50	191.12	0.192			VA05049846	0.62	6.5	
4	1	1.0	4.0	50							3.0											B292005	191.12	192.55	0.154			VA05049846	1.43	2.8	
3	1	2.0	3.5	40		328	chl	4		15.0	2.0		1.0					5.0	5.0			B292006	192.55	193.55	0.177			VA05049846	1.00	3.0	
							q	2																							
							cb	2																							
1	4	1.5	1.5	40																							selvage for both vein types				
1	6	1.0	1.0	50			chl	4		98.0			2.0									B292007	193.55	194.40	0.366			VA05049846	0.85	1.2	
							q	2																							
							cb	2																							

DRILL HOLE #: DG05-281C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION — Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		194.40	199.17	Unalt'd GND and qtz veins w/ selvages. At 194.7m, a xenolith of amphibolite, 5x4cm. Slickensides shown in chl/ser on fracture face 20° to CA. Qtz veins are mostly milky qtz on margins and selvage with cloudy grey qtz in centre.	1	2	1		1	
10		199.17	200.85	Carbonate-infused GND. Breaks along veins at 25°-35°. Regular fractures (no carb) at 65° to CA. Veins (noted), are somewhat silicified and difficult to see. Slickensides on 60° fract face, perpendicular (drawn) to CA.		2			2	
10		200.85	202.09	Unalt'd GND except selvage around qtz veins and sulphide vein. 3cm gouge zone at 201.61m		2		1	1	
10		202.09	204.72	V. fine grained GND. Colour is dark grey. Aphanitic, competent texture.			1			
10		204.72	222.50	Unalt'd GND. From 214.88 to 216.35m. Rich in carbonate veining on fractures. GND is 35% qtz, 25% bt, 20% feldsp, 20% hb. (E.O.H)		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 8 to June 11, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	veins/metre	VA05048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To								
6	1	1.0	4.0	35	120	2.0	q	2	0	1.0								5.0				B292008	194.40	195.07	0.060			VA05049846	0.67	9.0	
							s	2																							
6	1	1.0	4.0	35	120	2.0	q	2	0	1.0								5.0				B292009	194.40	195.07	0.059	PD/CA		VA05049846	0.67	9.0	
							s	2																							
																						B292010	STANDARD 6F		2.880	6F		VA05049846			
11	1	1.0	7.0	40	55	1.0	q	3		0.1	0.1		1.0						3.0			B292011	195.07	196.60	0.043			VA05049846	1.53	7.2	
							s	1																							
10	1	0.8	3.0	35	65	2.0	q	3		1.0	6.0		0.1					2.0	2.0			B292012	196.60	198.12	0.192			VA05049846	1.52	6.6	
							s	1																							
3	1	1.5	2.5	45		2.0	q	3		1.0	6.0		0.1					2.0	2.0			B292013	198.12	199.17	0.118			VA05049846	1.05	2.9	
							s	1																							
2	6	1.2	1.6	30		0.0				100								4.0													
5	1	1.0	5.0	60		2.0	q	3	0	3.0	0.1							4.0				B292014	199.17	200.85	0.400			VA05049846	1.68	3.0	
3	1	0.5	1.5	60		4.0	q	3	0	5.0	1.0							4.0				B292015	200.85	202.09	0.558			VA05049846	1.24	2.4	
1	6	0.5	0.5	60		10.0	q	4		30.0								4.0													
							chl	2																							
																						B292016	BLANK		<0.005			VA05049846			
4	1	1.3	3.5	45		3.0	q	4		3.0	0.1		0.1					4.0	3.0			B292017	202.09	203.45	0.485			VA05049846	1.36	2.9	
							chl	1																							
5	1	1.5	2.3	60	35	2.0	q	3	0	3.0			5.0						4.0			B292018	203.45	204.72	0.399			VA05049846	1.27	3.9	
1	6	0.4	0.4	45		3.0	q	4	0	40.0	40.0		10.0					3.0	4.0												
5	1	1.0	4.0	50		3.0	q	3	0		5.0							2.0				B292019	204.74	205.74	0.561			VA05049846	1.00	5.0	
5	1	1.0	4.0	45	60	0.0				10.0	3.0							3.0				B292020	205.74	207.26	0.269			VA05049846	1.52	3.3	
3	4	1.0	1.4	30		0.5	cb	1		0.0																					
7	1	1.0	5.0	55		1.0	q	3		0.1			0.1					4.0	4.0			B292021	207.26	208.79	0.276			VA05049846	1.53	4.6	
7	1	1.0	5.0	55		1.0	q	3		0.1			0.1					4.0	4.0			B292022	207.26	208.79	0.255	DUP		VA05049846	1.53	4.6	
8	1	1.0	7.0	40	55	1.0	q	4			5.0		5.0					4.0	4.0			B292023	208.79	210.31	0.109			VA05049846	1.52	5.3	
5	1	1.0	3.0	40	60	0.5	q	2			1.0		2.0					3.0	2.0			B292024	210.31	211.84	0.199			VA05049846	1.53	3.3	
2	1	0.5	1.0	60							2.0											B292025	211.84	213.36	0.023			VA05049846	1.52	1.3	
2	4	0.5	1.0	15		0.0				0.0																					
																						B292026	213.36	214.88	0.157			VA05049846	1.52	0.0	
1	1	1.0	1.0	55		0.5	q	3	0	5.0								4.0				B292027	214.88	216.41	0.051			VA05049846	1.53	0.7	
1	4	0.4	0.4	15		0.0				0.0																					
4	1	0.5	2.0	30	50	1.0	q	3	0		5.0		5.0					4.0	4.0			B292028	216.41	217.93	0.016			VA05049846	1.52	2.6	
							chl	1																							
4	1	0.5	2.0	30	50	1.0	q	3	0		5.0		5.0					4.0	4.0			B292029	216.41	217.93	0.015	PD/CA		VA05049846	1.52	2.6	
							chl	1																							
																						B292030	STANDARD 5E		1.450	5E		VA05049846			
3	1	1.5	3.0	50		1.0	q	3	0		4.0		5.0					2.0	4.0			B292031	217.93	219.46	0.055			VA05049846	1.53	2.0	
4	1	1.5	4.5	60	45	1.0	q	3	0	2.0	7.0		3.0					3.0	4.0			B292032	219.46	220.98	0.403			VA05049846	1.52	2.6	
7	1	1.0	5.0	50						2.0	10.0		2.0					3.0	4.0			B292033	220.98	222.50	0.186			VA05049846	1.52	4.6	
																								E.O.H.							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-282C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:

BEARING: 000 | DIP: -50°

DATE STARTED: 10-June-05 (7:00 PM) | DATE COMPLETED: 15-Jun-05

LOGGED BY: Kristian Whitehead & Dave Hladky

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459104 NORTHING: 7099244

COORD SYSTEM: NAD 83: EASTING: 458985 NORTHING: 7099428

NAD 27 (CORRECTED for historic grid): EASTING: 459074 NORTHING: 7099254

SECTION LINE(historic grid) = 459075 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing:

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B292708 - B292923

Requisition #: MASP448STRGOL.05Q | Date Shipped: 17-June-05

Lab Record #: VA05049598 | Date Received: 4-July-05

Sample Sequence: B292924 - B292979

Requisition #: MASP448STRGOL.05Q | Date Shipped: 21-June-05

Lab Record #: VA05052041 | Date Received: 11-July-05

Duplicates:	B292722, B292742, B292762, B292782, B292802, B292842, B292862, B292882, B292902, B292922, B292942, B292962
Preparation Duplicate/ Check Assay:	B292709, B292729, B292749, B292769, B292789, B292809, B292829, B292849, B292869, B292889, B292909, B292929, B292949, B292969
Standards:	B292710, B292730, B292750, B292770, B292790, B292810, B292830, B292850, B292870, B292890, B292910, B292930, B292950, B292970
Blanks:	B292716, B292736, B292756, B292776, B292796, B292816, B292836, B292856, B292876, B292896, B292916, B292936, B292956, B292976

FROM	TO	LITHOLOGY
6.10	191.80	GND
191.80	218.67	MSED
218.67	221.62	GND
221.62	237.80	MSED
237.80	240.53	GND
240.53	251.46	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
100.0	337.7	51.4	003.7	004.7
175.0	336.9	51.7	002.9	003.9
250.0	336.1	52.7	002.1	003.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 14-17, 2005	PAGE 1 of 18		
DRILL HOLE # : DG05-282C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		0.00	6.10	Casing (recovered 5.73-6.10m), GND description below.						
10	6.10-191.80	6.10	14.30	GND description as previous 2005 holes. sheeted vning essentially begins @ collar depth, vns are regularly @ ~40-45° to CA w/ avg widths of 0.25-1cm w/ dissem aspy (~trace to 3%) common. Vn spacing is currently @ 5-40cm apart. Fractures have limonite staining, lim is not pervasive.						
10		14.30	30.79	Core recovery is poor & core is severely broken, vning w/in coherent, larger pieces is not striking but subtle in appearance. Broken pieces don't have qtz pieces w/in, indicating veining. Thus conclusion remains @ modest vning system.						
10		30.79	35.05	Core remains the same GND mineralogy as from casing. Vning abundance is up to ~10-15/metre, but broken core makes precision of #'s difficult. Primary angle is 40° to CA w/ aspy the predominant sulphide w/in qtz vns.						
10		35.05	36.73							
10		36.73	37.17	Core is alt to light grey, mafic free, qtz eyes, sericite & chlorite present a soft, essentially a selvage for a vn, defined by ox'd sulphides & unox'd aspy ~5% & py ~1-2%. the interpreted angle to CA is @ 40° to CA. Some carb vnlets & clay.	2	3	2	2	1	
10		37.17	39.78							
10		39.78	39.86	Sandy/clay seam (unit). Core appears mildly bleached some (trace) aspy flecks.		1		2		
10		39.86	44.00	At ~42.43m is an area of GND pc's w/ a large amount of aspy & py. Orientation imperceptible but core pc's appear somewhat alt'd. Sulphides mildly ox'd: py @ ~3-5%, aspy @ 3%, difficult to be sure.		2	1	1	2	
10		44.00	44.20	Med alt'n zone due to two 1 & 1.5cm qtz & qtz/carb vns w/ ~5-10% sulphides (aspy & py). Chlorite hue on core. Core mafic devoid. Dull green/grey.	1	2	2		1	
10		44.20	53.34							

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048596 Return Samples
7	1	0.5	3.0	40	45								0.1									B292708	6.10	7.62	0.088			VA05049598	1.52	
7	1	0.5	3.0	40	45								0.1									B292709	6.10	7.62	0.096	PD/CA		VA05049598	1.52	
																						B292710	STANDARD 3C		0.093	3C		VA05049598		
9	1	1.8	6.3	40									0.1/2									B292711	7.62	9.14	0.124			VA05049598	1.52	
7	1	1.0	3.5	40									0.1/5									B292712	9.14	10.67	0.283			VA05049598	1.53	
3	1	1.0	2.5	35	40								0.1/3									B292713	10.67	12.19	0.206			VA05049598	1.52	
4	1	0.5	2.8	35	40								0.1									B292714	12.19	13.72	0.077			VA05049598	1.53	
2	1	0.3	0.3	20																		B292715	13.72	15.29	0.050			VA05049598	1.57	
																						B292716	BLANK		<0.005			VA05049598		
2	1	0.3	0.3	40									0.1									B292717	15.29	16.76	0.065			VA05049598	1.47	0.231
3	1	0.3	0.6	35	40								0.1									B292718	16.76	18.29	0.064			VA05049598	1.53	
7	1	0.5	4.0	35	40								0.1									B292719	18.29	19.81	0.081			VA05049598	1.52	
4	1	0.5	0.8	35									2.0									B292720	19.81	21.34	0.117			VA05049598	1.53	
6	1	1.0	4.0	35									0.1									B292721	21.34	22.86	0.122			VA05049598	1.52	
1	4	0.3	0.3	40																										
6	1	1.0	4.0	35									0.1									B292722	21.34	22.86	0.133	DUP		VA05049598	1.52	
1	4	0.3	0.3	40																										
3	1	0.3	2.0	30									0.1									B292723	22.86	24.38	0.195			VA05049598	1.52	
8	1	0.3		30	40								1.0									B292724	24.38	25.91	0.137			VA05049598	1.53	
													1.0									B292725	25.91	27.48	0.193			VA05049598	1.57	
													1.0									B292726	27.48	28.96	0.112			VA05049598	1.48	
8	1	0.8	0.8	40									1.0									B292727	28.96	30.48	0.110			VA05049598	1.52	
10	1	0.8	3.5	40									3.0									B292728	30.48	32.00	0.126			VA05049598	1.52	0.218
10	1	0.8	3.5	40									3.0									B292729	30.48	32.00	0.123	PD/CA		VA05049598	1.52	
																						B292730	STANDARD 4D		0.424	4D		VA05049598		
15	1	1.0	6.0	40									0.1									B292731	32.00	33.53	0.169			VA05049598	1.53	0.231
4	1	0.5	1.8	30	40								0.1									B292732	33.53	35.05	0.182			VA05049598	1.52	0.206
5	1	0.3	2.5	35	40								0.1									B292733	35.05	36.58	0.078			VA05049598	1.53	0.192
				40		44	3			2.0			2.0									B292734	36.58	37.68	0.211			VA05049598	1.10	0.269
6	1	0.5	4.0	35	40								1.0									B292735	37.68	39.62	0.106			VA05049598	1.94	0.226
																						B292736	BLANK		<0.005			VA05049598		
																						B292737	39.62	41.15	0.056			VA05049598	1.53	0.19
4	1	0.5	2.6	30	45	10.2				3.0			3.0									B292738	41.15	42.67	0.187			VA05049598	1.52	0.189
8	1	1.0	4.6	40		22	2	1		1.0			1.0									B292739	42.67	44.20	0.288			VA05049598	1.53	0.203
1	3	1.5	1.5	60	65	22	2	1		0.1			6.5																	
9	1	0.5	4.5	35	60					1.0			2.0									B292740	44.20	45.72	0.096			VA05049598	1.52	
4	1	0.3	2.0	33	68					0.1			0.1									B292741	45.72	47.24	0.033			VA05049598	1.52	
4	1	0.3	2.0	33	68					0.1			0.1									B292742	45.72	47.24	0.030	DUP		VA05049598	1.52	
																						B292743	47.24	48.77	0.024			VA05049598	1.53	
													0.1					2.0				B292744	48.77	50.29	0.136			VA05049598	1.52	
																						B292745	50.29	51.82	0.084			VA05049598	1.53	
6	1	0.3	1.3	40						0.1			0.1					4.0				B292746	51.82	53.34	0.070			VA05049598	1.52	

DRILL LOG LEGEND P1	DATE: June 14-17, 2005	PAGE 3 of 18	
DRILL HOLE # : **DG05-282C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		53.34	53.81	Intense alt'n zone, core is extremely bleached & reduced almost to clay ox'd py & aspy. Focus appears to be @ 53.42-53.47m where there's a digested carb/qtz vn @ 55-60° to CA. Sulphides are all concentrated w/in or predominantly adjacent, thus a large selvage from 53.34-53.81m.	2	4	2	3	3	
10		53.81	56.23	Core is salt & pepper textured; feldspars are reduced to white sericite & hornblendes remain as mafics. Core is like a strong clay.	1	4	1	3	1	
10		56.23	56.55							
10		56.55	57.34	Slickenside @ 10° to CA w/ gouge on one of slickenside surfaces. Srfc had ox'd aspy, perhaps py w/ slickened srfc.						
10		57.34	57.73							
10		57.73	57.91	Core becomes severely hydro alt'n etched yet mafics remain as salt/pepper texture. Qtz/carbs are broken to chalk-like hardness. Ox'd aspy & py present as graphite grey stringers/vns.		3	1	2	3	
10		57.91	58.79							
10		58.79	59.44	Slightly chlorite/sericite alt zone, essentially a continuous selvage section due to sheeted vning closeness.		2	2		1	
10		59.44	61.79							
10		61.79	63.40	Extreme hydrothermal alt'n window, core is v. bleached, yet some mafic zones exist. sericite & chlorite abundant, ox sulphides are visible abundant in zones, mostly looks aspy. v. broken core makes interpretation difficult. carbs abundant due to acid testing response. sulphides may be ~2-4% of core.		4	2	2	3	
10		63.40	66.50							
10		66.50	67.30	Selvage alt'd around gouge zone @ 67.06-67.14m. Gouge has ~1% py & >1% aspy. Gouge fizzes on acid, and is grey & white. Contact of gouge @ ~60-65° to CA.		4	2	5	2	
10		67.30	71.63	Core is v. broken but long shards along carb vnlets & stringers. Core is abundant on fracs w/ calcite & dolomite. Opinion is the predominant sulphides are coming in w/ carbs w/ py being the most noticed associated w/ carb vning. Carbs are often sheared w/ frac rock @ lower angles to CA.						
10		70.05	82.69	Core is v. broken, v. high amount of pc's w/ slickensides of polished aspy & py, which is mostly ox'd. Frac angles include 30° & 55° to CA.						
10		73.43	73.54	Faulted gouge/sand sized gravel w/ pure qtz pc's/slickensided pc's. Angle looks to be @ 20° to CA w/ ox'd aspy & py. Carb pc's also involved.		1		2	2	
10		74.18	75.48	Alteration zone, core is essentially a connected set of selvages. The focus of the selvages would be an 11cm thick carb dominant sulphide & minor qtz vn @ 35-40° to CA. Py continues to be dominant sulphide running w/ carb vns.		2	2		1	
				At 77.10m: the qtz vns have increased in size to 1cm or greater, and the first appearance of po (0.1%).						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

PAGE 4 of 18

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																		
						Selvages				Sulphides									Oxidation					Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA05048596 Return Samples
7	1	4.0	8.3	50	55					5.0			10.0					4.5				B292747	53.34	54.86	0.343		max aspy content	VA05049598	1.52	
4	1	1.3	3.6	55	60	24				5.0			20.0					3.0				B292748	54.86	55.56	0.420		max py	VA05049598	0.70	
4	1	1.3	3.6	55	60	24				5.0			20.0					3.0				B292749	54.86	55.56	0.422	PD/CA	max py	VA05049598	0.70	
																						B292750	STANDARD 1A		0.900	1A		VA05049598		
										0.1			0.1					4.5				B292751	55.56	56.39	0.264			VA05049598	0.83	
7	1	0.5	3.5	40	45	95	2.5		1	30			30.0									B292752	56.39	57.34	0.304			VA05049598	0.95	
2	1,3	0.3	0.5	45		12	2			2.0			50.0					4.5				B292753	57.34	57.91	0.221			VA05049598	0.57	
10	3	1.5	6.5	45		14	2			1.0			20.0									B292754	57.91	59.44	0.274			VA05049598	1.53	
6	3,1	0.5	2.3	40	45					0.1			1.0									B292755	59.44	60.96	0.160			VA05049598	1.52	
																						B292756	BLANK		<0.005			VA05049598		
6	1	0.5	4.3	40	45	1.5	1			1.0			5.0									B292757	60.96	61.79	0.171			VA05049598	0.83	
										1.0			3.0					4.5				B292758	61.79	62.11	0.154			VA05049598	0.32	
	3									0.1			2.0					4.5				B292759	62.11	62.48	0.159			VA05049598	0.37	
	3									2.0			2.0									B292760	62.48	63.40	0.175			VA05049598	0.92	
5	1	0.5	2.0	40	45								0.1									B292761	63.40	64.01	0.035			VA05049598	0.61	
5	1	0.5	2.0	40	45								0.1									B292762	63.40	64.01	0.062	DUP		VA05049598	0.61	
6	1	0.5	2.3	40	45					1.0			1.0									B292763	64.01	65.53	0.102			VA05049598	1.52	
2	4	0.3	0.5	40	20								5.0																	
2	4	0.1	0.3	30	40																	B292764	65.53	66.50	0.026			VA05049598	0.97	
																						B292765	66.50	67.30	0.199			VA05049598	0.80	
9	1	1.0	4.3	40									0.1									B292766	67.30	68.58	0.090			VA05049598	1.28	
6	1	0.8	2.5	50	60								0.1									B292767	68.58	70.10	0.136			VA05049598	1.52	
										0.5			0.5									B292768	70.10	71.63	0.092			VA05049598	1.53	
										0.5			0.5									B292769	70.10	71.63	0.090	PD/CA		VA05049598	1.53	
																						B292770	STANDARD 5E		1.545	5E		VA05049598		
5	1	0.5	3.5	35									0.5									B292771	71.63	73.16	0.070			VA05049598	1.53	
3	1	0.8	2.5	40									0.1									B292772	73.16	74.18	0.074			VA05049598	1.02	
1	3	11.0	11.0	45		50				6.5			1.0									B292773	74.18	74.68	0.355			VA05049598	0.50	
5	1	1.0	3.0	40	50	20	1.5			1.0			2.0									B292774	74.68	76.20	0.114			VA05049598	1.52	
1	4	0.8	0.8	50		20	1.5			40			0.5														broken to bits			
6	1	1.3	4.3	40	50	22	1.5			1.0			0.7									B292775	76.20	77.72	0.126		broken to bits	VA05049598	1.52	
																						B292776	BLANK				broken to bits	VA05049598		
6	1	3.0	8.8	50		10	1				0.1		0.1									B292777	77.72	79.25	0.065			VA05049598	1.53	
5	1	1.0	3.8	30		9	2		1		0.1											B292778	79.25	80.77	0.038		v. broken	VA05049598	1.52	
																						B292779	80.77	82.30	0.060			VA05049598	1.53	

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		82.94	83.24	Highly alt'd clay ream, sericite prevalent. White-grey clay, contact @ 82.94m @ 40° to CA, contact @ 83.24m @ 60°, slickenside srfc on either contact w/ competent core. Visible ox'd sulphide vnlets @ ~60° to CA.						
				At 83.24m: salt & pepper bleached/alt'd GND begins from this point. Core appears as acid bleached. Core is coherent, can be mushed by pushing heavy on it, indicating substantial sericite/clay content. Frac srfc's are commonly coated w/ slickensided ox'd sulphides.	2	4	1	2	4	
10		85.34	85.90	Core is very broken yet ox'd sulphides are abundant on fracs & fracs are abundantly slickensided. Py & aspy are discernable in some places.						
10		85.90	86.87	Alt'n selvage w/ slickensides on fracs w/ ox'd sulphide staining on srfc @ ~50° to CA.	2	3	2	1	0	
10		87.67	88.00	Same as above.	2	3	2	1	1	
10		91.44	93.19	Same as above w/ carb stringers on occasion. ~1% of core.	2	3	2	1	1	
10		93.52	94.01	Alt'n selvages contiguous due to qtz & carb vns @ ~60° to CA.	2	3	2	1	1	
10		95.63	96.01	Same as above.	2	3	2	1	1	
10		96.01	99.06	GND; mod to strong ser+ arg alt'n, locally wkly sheared to fault gg		3		4	2	
				At 97.86 - 97.87m = 0.5 cm py + aspy vn + qtz + cb						
				A few 1-2 cm dark mafic "xenos", commonly biotite (70%) + feld (+/- chl)						
				Tr aspy in selvages, disseminated						
				Local graphitic-pyritic slip surfaces at 60 deg						
10		99.06	100.58	Similar to above; slightly more sulphide veining		3		4	2	
				99.06 - 99.07m; qtz-cb vn @ 10 deg with 4% aspy + 0.3 cm qtz aspy vnlt (+/-cb) at 55 deg						
				At 99.2 m - graphic slip at 10 deg						
				At 99.53 - 99.57m, gougy zone (flt'd) at 30 deg to CA						
				Includes a 1 cm (99.54 - 99.55m) py-aspy +/- qtz vn						
				Commonly sheared to fract'd at 10-20 deg; highly alt'd, minor less alt'd GND zone						
				At 99.96 - 99.98m; similar py+/- py-aspy+/- qtz cb vn as abv; also with flt gg at 90 deg and at 20 deg to vn (at 70 deg)						
				At 100m fractured/sheared foliation at 60 deg and 20 deg						
10		100.58	102.11	As above; weakly sheared at 10-20 deg		2		3	2	
				At 105.73 - 105.74m = py + aspy + qtz/cb vn at 70 deg with a graphitic slip surface; possibly syngenetic/fracture filling; dominantly py on one side and aspy on other						
				At 101.2m fracture foliation at 10 deg to CA						
				At 101.96 to 101.97m = 1 cm fault gouge at 10 deg						
10		102.11	103.63	At 102.25m = fracture foliation at 20 deg and 120 deg		3		4	2	
				At 102.75m gougy surface (possibly shear - wk faulting) at 20 deg						
				At 102.75m slip surfaces (10cm spacing commonly) at 160 deg (relative to previous slip)						
				At 103.5m = fracture foliation at 5 deg; cb coated						
10		103.63	104.37	Moderate to strong alteration with shear in upper 20 cm		2		2	1	
				At 103.9m shear fractures at 20 degrees						
				At 103.95m fracture foliation at 60 deg (150 deg)						
				At 104.2m pyritic slip surface at 60 deg (150 deg)						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2006

LOGGED BY: D. Hladky & K. Whitehead

PAGE 6 of 18

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval							
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048696 Return Samples
																						B292780	82.30	83.82	0.121			VA05049598	1.52	
3	1	1.0	1.6	45	50	1.52							2.0									B292781	83.82	85.34	0.066			VA05049598	1.52	
3	1	1.0	1.6	45	50	1.52							2.0									B292782	83.82	85.34	0.107	DUP	v. broken, poor recovery, pc's only	VA05049598	1.52	
2	1	1.5	2.5	70	75	1.52							3.0									B292783	85.34	86.87	0.362		v. broken, poor recovery, pc's only	VA05049598	1.53	
3	1	0.1	0.3	60	70	0.5	1						0.1									B292784	86.87	87.67	0.062			VA05049598	0.80	0.162
4	1	1.5	2.8	50						0.1			0.1		0.1							B292785	87.67	88.00	0.144			VA05049598	0.33	
1	4	0.3	0.3	50									0.1		0.1														
3	1	0.3	0.8	50	55					0.1			0.1									B292786	88.00	88.39	0.371			VA05049598	0.39	0.208
																						B292787	88.39	91.44	0.062			VA05049598	3.05	0.282
8	1	1.0	3.8	50		1.5	2			0.1			1.0									B292788	91.44	92.96	0.175			VA05049598	1.52	0.243
8	1	1.0	3.8	50		1.5	2			0.1			1.0									B292789	91.44	92.96	0.180	PD/CA	too altered to see	VA05049598	1.52	
																						B292790	STANDARD 2B		3.280	2B		VA05049598		
5	1	1.0	4.0	60		18	2						0.1									B292791	92.96	94.17	0.151			VA05049598	1.21	0.123
3	4	0.8	1.5	60		16	3	2		0.1			0.1																
1	1	0.8	0.8	50									0.5									B292792	94.17	95.63	0.084		core is too broken	VA05049598	1.46	0.173
1	3	2.0	2.0	50		37	3.5	2		2.0			2.0									B292793	95.63	96.01	0.175			VA05049598	0.38	
3	3	0.3	0.8	40	45								0.1									B292794	96.01	97.54	0.074			VA05049598	1.53	0.339
1	6	0.1	0.1	60		9.0	2			2.0			2.0																
4	3	0.3	3.0	45		2.0	s,cb,arg	3		5.0			4.0																
1	6	0.5	1.0	45		1.0	cb	4	0	30.0			5.0									B292795	97.54	99.06	0.236		0.5 cm py + aspy vnlt; qtz/cb/ +/- py & aspy vnlts	VA05049598	1.52	0.501
																						B292796	BLANK		<0.005			VA05049598		
4	6	2.0	4.0	45	60	2.0	q,cb,arg	3	0	5.0			3.0									B292797	99.06	100.58	0.347			VA05049598	1.52	0.395
1	3	1.0	1.0	10		0.5	q,cb,arg	2	0				4.0																
2	6	1.0	1.5	70		3.0	3	4	1	40.0			5.0										(99.54 | 99.55)			py/aspy qtz-cb vn			
2	6	2.0	2.0	70		2.0	3	4	1	45.0			5.0										(99.96 | 99.98)			py/aspy + qtz/cb vn			
4	3	0.8	4.0	60	50	3.0	3	4	0	3.0			2.0									B292798	100.58	102.11	0.231		0.5% diss aspy	VA05049598	1.53	0.449
1	6	0.5	0.5	70		2.0	3	3	0	45.0			30.0										(105.73 | 105.74)						
2	3	0.3	2.0	50	45	3.0	q/cb/arg	4	0	2.0			0.5									B292799	102.11	103.63	0.048			VA05049598	1.52	0.417
2	3	1.0	3.0	60	45	3.0	q/cb/arg	3	0	3.0			0.5									B292800	103.63	104.37	0.054			VA05049598	0.74	0.233

DRILL HOLE # : DG05-282C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		104.37	105.60	GND; less alt'd; less shr; common 1-2mm qtz-py-aspy-cb vnlts at 60 deg		2		1	1	
10		105.60	106.68	Highly alt'd GND; possibly shear/fault zone at 105.65 to 105.7m; 105.7 to 105.8m highly altered with moderate shear at 45 deg; At 105.6 -105.65m py+aspy+qtz/cb veins (2 to 3) up to 1cm in hanging wall of high alteration/ shear zone; lower contact to this zone at 106.2m at 45 deg		3		5	2	
10		106.68	107.20	As above		3		5	2	
10		107.20	108.20	Moderately altered GND; trace disseminated py in selvages; At 107.6m = slip face at 60 deg to core axis		2		2	1	
				At 107.9 - 108.0m gougy zone, possibly a flt; high argillite alt'n with tr-1% diss py; upper contact at 70 deg; common slip faces at 60 deg						
10		108.20	109.72	Moderately alt'd GND; wk shr fracturing; at 108.25m shear foliation at 60 deg; increasingly alt'd towards the base; more rubbly		2		2	2	
10		109.72	114.80	Very poor recovery; only small to 10 cm pieces; qtz + aspy + py stringers		3		1	2	
				At 114.66 - 114.8m gouge zone sheared to moderately faulted at 60 deg; 1-3mm stringers throughout						
10		114.80	114.97	Sulphide - Quartz vein at 60 deg; bottom contact of gougy shear and highly alt'd zone at 60 deg; v f g to 3mm grains; shear/fault related?		2		2	1	1
10		114.97	121.92	Moderately to weakly alt'd; At 115.5m slip face with minor gouge at 30 deg to CA		3		2	1	
				Sheared to gougy sections; moderately fractured with gouge in btw pieces of broken GND						
				At 117.3m = pyritic slip at 40 deg						
				At 117.6m = fracture foliation at 30 deg; 118.6m - 118.87m = broken core with cb on fracture surfaces; At 118.95m fracture foliation at 10 deg and 160 deg						
				At 119.5 - 119.7m, 4 X 0.2 - 0.3 cm py +/- aspy vnlts at 60						
				At 119.8 - 119.9m = minor gouge to shr at 20 deg to CA						
				At 120.45 - 121.4m = multiple <1cm qtz (sheeted?) vnlts at 30 to 25 deg						
				At 120.65m slip at 150 deg relative to vnlts; planar with sericite						
				At 121.18m - pyrite vnlt at 70 deg at 90 deg to quartz veinlets (py + aspy + aspy + qtz)						
				At 121.65 - 122m = broken core						
10		121.92	123.02	GND, moderately altered due to quartz veinlets' local pyritic fracture filling (1mm)		4		3	2	
				At 122.6m at 130 deg (relative to qtz vnlts) is qtz-carb vnlt (o.3mm) with tr py						
10		123.02	123.99	Shear GND; light green; sheared to gg (irregular); quartz-py _ aspy vns at upper and lower contacts; minor gouge at upper and lower contacts as well		4		3	2	
				At 123.99m pyritic slip at 43 deg to CA parallel to pyrite vein						
10		123.99	126.49	Slightly less alt'd than prev; multiple quartz (+/- cb) vnlts with aspy-py; at increasingly low angle to CA		3		3	2	
				At 124.57m sericitic slip face at 15 deg, parallel to veinlets						
				Core moderately broken; mnr veining; at 125.05m slip at 60 deg						
10		125.47	126.49	Increased alteration of GND; common low angle slip/shr faces and some veining; At 125.47 - 125.49m = gougy shear at 45 deg to CA; At 125.98m slip at 10 deg to CA with stria at 60 deg		4		3	2	
10		126.49	128.40	Less alt'd GND; low angle veins moderate alteration; qtz +/- py and aspy		2		1	1	
10		128.40	129.35	Increasingly altered GND due to qtz vn, 1 cm with py on margins		4		3	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA06048696 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To						
4	1	0.3	2.5	50	45	0.5	q/cb	2	0	5.0			0.3									B292801	104.37	105.60	0.357			VA05049598	1.23	
4	1	0.3	2.5	50	45	0.5	q/cb	2	0	5.0			0.3									B292802	104.37	105.60	0.407	DUP		VA05049598	1.23	
2	6	1.0	2.0	60		2.0	arg/cb	5	0	50.0			20.0									B292803	105.60	106.68	0.053			VA05049598	1.08	
3	4	0.5	3.0	30		1.0	cb/arg	4	0	0.5													(105.6	105.65)			pyrite +/- aspy ant qtz/cb vnlts			
2	3	0.3	1.0	60		1.0	cb/arg	3	0	0.5												B292804	106.68	107.20	0.061			VA05049598	0.52	0.3
3	3	0.3	2.0	60		1.0	cb/arg	3	0	2.0			0.2									B292805	107.20	108.20	0.101			VA05049598	1.00	0.417
2	3	0.2	0.5	60		2.0	qtz/ser/cb	3		0.2												B292806	108.20	109.72	0.311			VA05049598	1.52	0.916
4	1	0.3	4.0	50		0.5	q/cb	2		5.0			8.0									B292807	109.72	111.25	0.302			VA05049598	1.53	0.878
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292808	111.25	112.78	0.067			VA05049598	1.53	<0.005
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292809	111.25	112.78	0.076	PD/CA		VA05049598	1.53	
																						B292810	STANDARD 5E		1.520	5E		VA05049598		
1	1	0.2	0.2	50		0.5	q/cb	2		3.0			2.0									B292811	112.78	114.30	0.066		Qtz +/- py vnlts	VA05049598	1.52	0.483
2	6	0.2	0.5	60		0.5	cb/arg	3		25.0			5.0									B292812	114.30	114.80	0.140		Vnlts in gouge	VA05049598	0.50	0.424
1	6	12.0	12.0	60		5.0	qtz/cb	4		50.0			10.0									B292813	114.80	114.97	1.785		High Sulphides	VA05049598	0.17	
1	1	5.0	5.0	60		5.0	qtz	2		10.0			3.0																	
2	2	0.6	1.5	45	60	3.0	cb/arg	3		0.8			0.1									B292814	114.97	115.82	0.118			VA05049598	0.85	
2	3	0.2	0.8	50			cb/arg	3		2.0			0.5									B292815	115.82	117.35	0.138			VA05049598	1.53	0.521
1	6	1.5	1.5	45		5.0	se/cb/arg	3		8.0			4.0		4.0								(116.65	116.67)			Py + sph + qtz/cb vn			
																						B292816	BLANK		<0.005			VA05049598		
4	1	0.5	2.0	60	50	0.5	qtz/ser	2		20.0			2.0									B292817	117.35	118.87	0.195			VA05049598	1.52	0.691
4	6	0.3	1.2	60		1.5	se/cb/qtz	3		60.0			5.0									B292818	118.87	120.40	0.171		py/aspy vnlts; mnr sulph in qtz vnlts	VA05049598	1.53	0.591
5	1	0.4	3.0	50	60	0.5	ser/qtz	1		3.0			0.8																	
10	1	0.8	5.0	30	25	5.0	se/qtz	2		3.0			0.8									B292819	120.40	121.92	0.189		multiple qtz +/- py vnlts	VA05049598	1.52	0.886
2	6	0.3	0.8	30		0.6	se/qtz/cb	2		50.0			4.0										(121.18				py/aspy +/- qtz vnlt			
2	6	0.3	0.4	70		1.5	se/arg/qtz	2		60.0			15.0																	
4	1	0.8	3.0	40	30	3.0	ser/erg/qtz	3		3.0			1.5									B292820	121.92	123.02	0.160			VA05049598	1.10	0.524
2	3	0.3	0.5	130		1.0	cb/qtz/ser	2		0.8																				
1	1	7.0	7.0	30		5.0	arg/cb/ser	4		18.0			6.0									B292821	123.02	123.99	0.466			VA05049598	0.97	0.516
1	1	7.0	7.0	30		5.0	arg/cb/ser	4		18.0			6.0									B292822	123.02	123.99	0.772	DUP		VA05049598	0.97	
																							(123.02	123.08)			qtz-py-aspy vn, upper contact	VA05049598		
1	3	2.5	2.5	43		3.0	arg/cb/ser	3		22.0			4.0										(123.96	123.99)						
5	1	0.6	4.0	20	30	0.5	ser/cb/arg	3		2.0			3.0									B292823	123.99	124.97	0.340			VA05049598	0.98	
3	1	0.4	2.0	50		1.0	ser/cb/arg	3		0.8			0.4									B292824	124.97	125.47	0.266			VA05049598	0.50	0.707
3	1	0.5	2.0	20	30	1.5	ser/cb/arg	3		5.0			3.0									B292825	125.47	126.49	0.470		Qtz vnlts +/- py, aspy vnlts, low angle	VA05049598	1.02	
2	1	0.7	1.5	20		2.0	ser/cb/arg	2		4.0			1.5									B292826	126.49	128.07	0.155			VA05049598	1.58	0.703
1	1	0.3	0.3	20		1.0	ser/cb/arg	2		4.0			1.5									B292827	128.07	128.40	0.179			VA05049598	0.33	0.709
1	1	1.0	1.0	25		10.0	ser/cb/arg	4		4.0			2.0									B292828	128.40	129.35	0.065			VA05049598	0.95	
1	1	1.0	1.0	25		10.0	ser/cb/arg	4		4.0			2.0									B292829	128.40	129.35	0.060	PD/CA		VA05049598	0.95	
																						B292830	STANDARD 6F		2.830	6F		VA05049598		

DRILL HOLE # : DG05-282C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		129.35	131.70	Slightly less altered GND than prev; At 129.85m = low angle quartz vns (20 deg)		4		2	2	
				At 131.1m quartz-cb vnlts at 35 deg; At 131.2m low angle qtz/cb fracture filling with ser slip faces at 15 deg; At 131.25m at 140 deg, quartz open space filling; euhedral quartz xtls in 1 cm vug						
10		131.70	132.05	Mnr faulting with associated veining		4		3	3	
				At 131.7 - 131.76m = Quartz vein with high sulphides (py gen; at lower margin)						
10		132.05	133.10	Less alt'd than prev; less shr; carb-qtz vn with trace sulphides at low angle (15 deg) to CA		3		2	2	
10		133.10	144.45	Less alt'd than prev; still dk bt, occasional alt'n adj to vein sets; relatively less fractured and sheared than prev		1		1	1	
				At 135.1 - 135.14m = FLT GG at 40 deg to CA; ser-arg-carb alt'd; no vis min; At 135.63m = graphitic slip with striae at 30 deg; face at 15 deg						
				Sheeted veins of qtz +/- coarse grained aspy/py; spacing btw 5 and 20cm; <1cm diam; At 136.58m graphitic slip face at 25 deg with straie at 20 deg; tr py; At 136.6 - 136.75m 0.2 mm fracture filling by carb-arg (clay) at 150 deg relative to the previous slip face						
				Generally uniform; weakly alt'd GND with mnr alteration associated with thin qtz vns (+/- tr py-aspy); at 138.38m slip shr face @ 25 deg; mnr carb coatings						
				Sim to abv						
				Mnr veining wi a "xenolith" of dk mafic (perhaps pot alt'd?) (78% bt + qtz + feld)						
				Similar to abv; slightly more vnlts; (qtz +/- py/aspy) gen at 30 deg to CA						
				Similar to abv; slightly more aspy in strings and local disseminations; irregularly fractured and slightly more alt'd from 143.76m						
				At 144.45 - 144.66m, moderate ser-cb-arg alt'n assoc'd with qtz-aspy-py vn at 40 deg to CA		3		2	2	
10		144.66	147.35	144.66 - 147.35 Weakly to locally alt'd GND; 145.4 - 145.75m = multiple qtz +/- py vnlts, vein to blotchy aspy selvages (0.7%)		1		1	1	
10		147.35	148.42	Increased alteration due to mnr shearing; mnr - tr qtz +/- py veining		3		3	3	
10		148.42	150.55	Locally wkly alt'd GND; generally unalt'd; mnr qtz +/- py/aspy vnlts		1		1	1	
10		150.55	153.00	Generally wkly to mod'ly ser-cb-arg alt'd; local mnr zones of relatively unalt'd GND		2		2	2	
				151.3 - 151.32 = Shr to gouge; high argillic alteration at 20 deg to CA					4	
				151.6 Slip/Shr plane at 30 deg to CA; slightly pyritic and gougy						
10		153.00	153.92	Moderately alt'd GND due to qtz - py/aspy vn (grey qtz); At 153.63 - 153.68m; 153.72 - Shr/slip at 30 deg parallel to vn		3		4	2	
				Locally blotch aspy/py in selvages (<2%)						
10		153.92	156.40	Weakly to locally relatively unaltered (grey) GND		2		2	1	
				At 154.15m - black (pyritic) slip at 40 deg						
10		156.40	156.97	Sericite altered GND; increasingly altered towards base of interval		3		2	1	
				At 156.76 - 156.78m = Qtz cb vn wi 1-3% py/aspy						
10		156.97	157.50	Weakly alt'd GND		2		1	1	
				At 157.5m = slip (pyritic face) at 40 deg						
10		157.50	159.40	Moderately to strongly alt'd GND; wkly sheared; shr fracts commonly filled with cb/qtz; some qtz +/- py veining; core soft		3		4	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA06048596 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	0.8	4.0	10	20	10.0	se/c	3		0.5			0.5									B292831	129.35	131.06	0.198			VA05049598	1.71	0.683
2	3	0.5	1.5	10	35	1.5	cb	3		0.4			0.2																0.684
1	3	0.5	1.5	10	35	105.0	ser/cb	3		0.4			0.2									B292832	131.06	131.70	0.233			VA05049598	0.64	0.57
1	1	1.0	1.0	15		2.0	se/arg/cb	3		0.5			0.3									B292833	131.70	132.05	0.729			VA05049598	0.35	
1	1	6.0	6.0	20		1.0	ser/cb/arg	2		20.0			2.0										(131.7	131.76)			Qtz and py at upper contact, flt'd?			
2	1	0.8	2.0	15	20	1.0	se/cb/arg	2		0.5			0.4									B292834	132.05	133.10	0.122			VA05049598	1.05	0.963
2	4	1.0	1.0	15		2.0	cb/ser/arg	3		0.8			0.6										(132.4	132.41)			Cb-qtz vn)			
3	1	0.6	2.0	15		0.8	se/cb/arg	2		0.8			0.4									B292835	133.10	134.11	0.086			VA05049598	1.01	
1	1	1.0	1.0	140		0.5	se	1		0.5			0.4										(134.45	134.46)			Qtz vein			
																						B292836	BLANK		<0.005			VA05049598		
1	1	1.0	1.0	30		5.0	se/cb/arg	2		0.5			0.4									B292837	134.11	135.64	0.091			VA05049598	1.53	0.74
1	1	1.0	1.0	30		5.0	se/cb/arg	2		0.5			0.4										(134.55	134.56)			Qtz vn			
5	1	0.5	5.0	20	25	0.5	se/cb/arg	2		1.5			1.5									B292838	135.64	137.16	0.107			VA05049598	1.52	0.983
v	1	0.3	1.2	35	30	0.5	se/cb/arg	2		0.4			0.4									B292839	137.16	138.68	0.076			VA05049598	1.52	0.855
6	1	0.3	2.0	40	35	0.5	se/cb/arg	2		1.0			0.5									B292840	138.68	140.21	0.186			VA05049598	1.53	0.446
2	1	0.3	0.5	40		0.5	se/qtz/cb	2		1.0			0.5									B292841	140.21	141.73	0.198			VA05049598	1.52	0.366
2	1	0.3	0.5	40		0.5	se/qtz/cb	2		1.0			0.5									B292842	140.21	141.73	0.190	DUP		VA05049598	1.52	
6	1	0.3	2.0	30		0.5	ser/qtz	2		1.0			1.0									B292843	141.73	143.26	0.165		Qtz py/aspy stringers	VA05049598	1.53	0.361
																						B292844	143.26	144.45	0.410		Qtz py/aspy stringers	VA05049598	1.19	
1	1	1.0	1.0	40		10.0	se/cb/arg	2		3.0			5.0									B292845	144.45	144.66	0.807			VA05049598	0.21	
																							(144.55	144.56)			Qtz aspy vn			
8	1	0.6	4.0	42	30	0.5	qtz/ser/cb	1		0.5			0.7									B292846	144.66	146.10	0.186		Small qtz py/aspy vnlts	VA05049598	1.44	0.282
5	1	0.6	3.0	25		0.5	qtz/ser/cb	1		0.5			0.5									B292847	146.10	147.35	0.116		Small qtz py/aspy vnlts	VA05049598	1.25	0.298
2	3	0.5	1.0	30		10.0	se/cb/arg	1		0.5			0.5									B292848	147.35	148.42	0.052			VA05049598	1.07	0.281
2	3	0.5	1.0	30		10.0	se/cb/arg	1		0.5			0.5									B292849	147.35	148.42	0.052	PD/CA		VA05049598	1.07	
																						B292850	STANDARD 3C		0.094	3C		VA05049598		
4	1	0.4	2.0	30		1.0	se/qtz	2		0.5			0.4									B292851	148.42	149.35	0.042		mnr qtz +/- py, aspy vnlts	VA05049598	0.93	
3	1	0.4	2.0	30		1.0	ser/qtz	2		0.5			0.4									B292852	149.35	150.55	0.038			VA05049598	1.20	0.215
3	1	0.2	1.0	30		1.0	se/qtz	3		0.5			0.4									B292853	150.55	150.88	0.064			VA05049598	0.33	
2	6	0.3	0.5	30		2.0	se/cb/qtz	2		10.0			5.0									B292854	150.88	152.40	0.038			VA05049598	1.52	0.157
2	1	0.2	1.0	30		1.0	ser	1		0.5			0.4										(151.6	151.65)			py/aspy strgrs			
2	1	0.2	1.0	30		1.0	qtz/ser	1		0.5			0.4									B292855	152.40	153.00	0.080			VA05049598	0.60	0.219
																						B292856	BLANK		<0.005			VA05049598		
5	1	0.3	3.0	40	30	2.0	ser/arg/cb	4		5.0			3.0									B292857	153.00	153.92	0.333			VA05049598	0.92	
1	1	5.0	5.0	30		10.0	ser/arg/cb	4		5.0			4.0										(153.63	153.68)			Qtz aspy/py vein at 30 deg			
3	6	0.1	0.2	30		0.5	se/cb/arg	2		20.0			2.0									B292858	153.92	155.45	0.077			VA05049598	1.53	0.33
1	1	0.8	2.0	40		3.0	se/arg/cb	2		2.0			1.0									B292859	155.45	156.40	0.017			VA05049598	0.95	0.302
																							(156.39	156.4)			Qtz +/- py/aspy vn			
2	1	0.2	0.5	25		2.0	se/cb	3		0.4			0.3									B292860	156.40	156.97	0.027			VA05049598	0.57	
1	3	1.5	1.5	25		3.0	se/cb	3		1.5			0.7										(156.76	156.78)						
2	1	0.1	0.3	25		0.5	se/cb	2		0.5			0.5									B292861	156.97	157.50	0.019			VA05049598	0.53	0.469
2	1	0.1	0.3	25		0.5	se/cb	2		0.5			0.5									B292862	156.97	157.50	0.022	DUP		VA05049598	0.53	
3	1	0.5	1.5	25		2.0	se/arg/cb	4		0.5			0.4									B292863	157.50	158.50	0.047		Mnr qtz +/- py vnlts	VA05049598	1.00	
10	4	0.2	5.0	1		0.5	cb	2																						
2	1	0.5	1.5	25		2.0	se/arg/cb	2		0.5			0.5									B292864	158.50	159.40	0.033		Mnr qtz +/- py vnlts	VA05049598	0.90	0.243

DRILL LOG LEGEND P1	DATE: June 14-17, 2005	PAGE 11 of 18		
DRILL HOLE # : DG05-282C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		159.40	161.90	Higher Cb alt'n; core more competent (hard); increased veining		2		2	4	
				Increased silica; local pyrite stringers/fracture filling						
				161.35 - 161.41m = 2 X 0.5 cm zones of high pyrite mineralization in highly altered GND; irreg, though generally at 30-40 deg						
10		161.90	164.45	Non to locally weakly unaltered GND		1		1	1	
				From 162.75 to 162.76m: Qtz vein (gy clr qtz) with 2% aspy ± py. Noted alt'n is local.		2		3	1	
10		164.45	170.80	Highly argillic altered GND; common unaltered biotite; generally soft; rare veining; not a fault		3		5	2	
				gouge; rare veins						
				Core slightly more competent; less alt'd than previous and slightly less veining						
10		170.80	171.22	Sericite +/- argillic altered GND adjacent to 2-3cm qtz vn (with up to 3-4% aspy); no mineralization visible in the selvage		2		1		
10		171.22	173.12	Weakly to locally strongly alt'd GND		2		3	2	
				GND more competent adj to qtz vnlts, becoming more argillic alt'd within 10cm of vein; commonly cb +/- qtz on fracture surfaces; sampled relative to larger veins/veinlets		3		4	3	
				At 172.38m aspy-py coated (slip?) surface at 35 deg						
				Qtz vein at 35 deg (172.84 - 172.87m) with dk py; blebs of aspy and py-aspy coated lower contact; dominantly arg-ser-cb alt'n on either side						
10		173.12	175.00	Sericite alteration dominant with locally increased argillic alteration;		3		3	2	
				Nice py-aspy bearing vn (with shear?) at 173.2 - 173.25; slip/shr surfaces at 50 deg; py-aspy coated; dominantly se alt'n						
				Qtz-aspy-py vein; grey to white qtz, sulphides dominantly on margins with 2-3 mm and of spy through middle; black py (possibly due to shr) on margins						
10		175.00	175.86	Weakly ser-chl-arg alt'd GND with multiple thin qtz vnlts; increasing argillic alt'n towards the base		1	2	1	1	
10		175.86	177.40	High argillic alteration; moderately - highly gougy, some quartz veining		3	1	4	2	
10		177.40	177.53	White to grey qtz vn, 3% aspy wi 1-2% py at margins						
10		177.53	178.65	Argillic + sericitic alt'd GND (Lt gn to white)		3		3	2	
10		178.65	179.44	Relatively unaltered GND		1		1		
10		179.44	180.60	Intensely arg/ser alt'd GND due to white quartz veining, poor mineralization		4		5	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar,, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																							
						Selvages				Sulphides										Oxidation					Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA05048696 Return Samples
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other			From	To						
6	4	0.2	3.0	25		0.5	cb/ser	2		1.0													B292865	159.40	160.38	**0.033**			VA05049598	0.98	
3	6	0.2	1.0	25		1.0	cb.ser.qtz±	3		80.0			2.0																		
3	6	0.2	1.0	25	30	0.5	cb/qtz	3		80.0			2.0										B292866	160.38	161.90	**0.106**			VA05049598	1.52	0.285
2	6	0.5	1.5	30		0.5	cb/qtz	3		80.0			2.0																		
4	4	0.3	1.5	120		0.5	qtz.cb	3		0.5			0.2																		
3	1	1.0	2.5	60		0.5	se/qtz	2		0.7			0.5										B292867	161.90	163.07	**0.110**			VA05049598	1.17	0.274
3	1	1.0	1.0	60		0.2	qtz/cb	2		0.3			0.5											(162.75	162.76)						
3	1	1.0	0.3	60		0.5	se/cb	2		0.5			0.5										B292868	163.07	164.45	**0.091**			VA05049598	1.38	0.308
3	1	1.0	0.3	60		0.5	se/cb	2		0.5			0.5										B292869	163.07	164.45	**0.096**	PD/CA		VA05049598	1.38	
																							B292870	STANDARD 2B		**3.200**	2B		VA05049598		
3	3	0.1	0.5	45		0.5	arg/cb/se	4		0.5			0.2										B292871	164.45	165.23	**0.072**		trace veining	VA05049598	0.78	0.303
2	1	0.2	1.0			0.5	arg/cb/se	4		1.0			1.0										B292872	165.23	166.12	**0.086**			VA05049598	0.89	
1	1	0.5	0.5			0.5	cb/arg/ser	4		2.0			3.0											(165.8	165.81)						
3	1	0.8	4.0	40		0.5	cb/ser/arg	4		1.5			0.8										B292873	166.12	167.64	**0.094**			VA05049598	1.52	0.266
3	1	0.6	3.0	40		1.0	cb/ser/arg	4		1.0			0.5										B292874	167.64	169.16	**0.058**			VA05049598	1.52	
2	1	0.7	4.0	40	45	0.5	ser/cb/otz/arg	2		1.0			0.6										B292875	169.16	170.41	**0.100**			VA05049598	1.25	
																							B292876	BLANK		**<0.005**			VA05049598		
																							B292877	170.41	170.80	**0.169**			VA05049598	0.39	
2	1	3.0	4.0	45		11.0	se/cb/arg	4		1.0			4.0										B292878	170.80	171.22	**0.407**			VA05049598	0.42	
2	1	3.0	3.0	45		10.0	ser	4		1.5			4.0											(170.9	170.93)			Good qtz-aspy vein			
3	1	1.3	4.0	55		5.0	arg/ser/cb	4		1.5			1.5										B292879	171.22	172.21	**0.035**		Qtz py/aspy vnlts	VA05049598	0.99	
3	1	1.0	4.0	45		2.0	se/arg/cb	3		1.5			1.5										B292880	172.21	172.84	**0.367**			VA05049598	0.63	
2	1	3.0	4.0	35		10.0	ser/arg/cb	4		2.0			1.5										B292881	172.84	173.12	**0.213**			VA05049598	0.28	
1	1	3.0	3.0	35		10.0	se/arg/cb	4		3.0			1.5											(172.84	172.87)						
																							B292882	172.84	173.12	**0.166**	DUP		VA05049598	0.28	
3	1	5.0	5.5	50		11.0	se/cb/arg	3		7.0			2.0										B292883	173.12	173.50	**22.800**			VA05049598	0.38	
1	1	5.0	5.0	50		10.0	se/cb/arg	3		7.0			2.0											(173.2	173.25)						
2	1	4.0	5.0	60		10.0	arg/se/cb	4		4.0			5.0										B292884	173.50	173.87	**0.376**			VA05049598	0.37	
1	1	4.0	4.0	60		10.0	se/cb/arg	4		4.0			5.0											(173.74	173.78)						
2	1	0.2	0.8	45		0.5	se/cb/arg	2		0.3			0.2										B292885	173.87	175.00	**0.123**			VA05049598	1.13	
4	1	0.4	1.5	5	5	0.5	ser/qtz/chl	2		0.4			0.3										B292886	175.00	175.86	**0.072**			VA05049598	0.86	
5	1	0.6	4.0	45		10.0	arg/ser/chl	4		0.9			0.6										B292887	175.86	177.40	**0.166**		Qtz vnlts with py/aspy	VA05049598	1.54	
1	1	13.0	13.0	50		10.5	arg/se/cb	3		1.5			3.0										B292888	177.40	177.53	**0.056**		Qtz vn with 1.5 % py + 3% aspy	VA05049598	0.13	
1	1	13.0	13.0	50		10.5	arg/se/cb	3		1.5			3.0										B292889	177.40	177.53	**0.052**	PD/CA	Qtz vn with 1.5 % py + 3% aspy	VA05049598	0.13	
																							B292890	STANDARD 7G		**4.510**	7G		VA05049598		
2	1	0.5	1.0	50		10.5	arg/ser/chl	3		0.5			0.4										B292891	177.53	178.65	**0.090**			VA05049598	1.12	
1	6	0.4	0.4	50		1.0	arg/ser	4		70.0			3.0																		
3	1	0.2	1.0	40	30	0.5	ser/arg	1		1.0			0.4										B292892	178.65	179.44	**0.093**			VA05049598	0.79	
3	1	6.0	10.0	40		11.0	arg/ser	4		2.0			0.5										B292893	179.44	180.60	**0.143**			VA05049598	1.16	
1	6	0.3	0.3	130		1.0	arg/ser/cb	3		60.0			3.0																		
1	1	3.0	3.0	40		10.5	arg/ser/cb	4		2.0			0.5											(180.42	180.48)			Qtz vn wi mnr py/aspy			

DRILL HOLE # : DG05-282C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.60	185.06	Weakly to locally moderately alt'd GND; alt'd adj to veins/veinlets		1		1	1	
				selvages' alt'n:		2		3	2	
				At 182.56 - 182.80m = Qtz aspy vein set at 30 deg to CA; 60% aspy in vnlt; wi qtz						
				Qtz vein with coarse grained py/aspy up to 12% overall; sulphides commonly on margins, sample includes 10cm of alt'd GND (ser+cb+arg alt'n)						
10		185.06	186.37	Weak sericite-argillic alteration of GND; 1-2 qtz-aspy +/- py vnlts		1		1	1	
10		186.37	187.04	Similar GND to prev; wi multiple 1-6 cm "dark" " xeno's(?)" may be potassic alt'd GND (bt +/- hb +/- feld = dominant mins; weak silicic (silicification) rim around "xenos"; no increased mineralization assoc'd		1	1	1	1	3
10		187.04	189.37	Weak sericite +/- arg alt'd GND		1		1	1	
				Sheeted vnlts of qtz and aspy-qtz; gen 0.5 cm; gen at 30-40 deg to CA; up to 80% aspy (best btw 187.65 - 188.6m)		2		2	1	
				Sim to abv; less intense veining; with less sulphides and frequency of vnlts						
10		189.37	190.00	Sim to 186.37-187.04 interval; Potential potassic alt'd GND "xenos" = 15% of core; some aspy rimming on xeno as well as a 0.7mm veinlet of 80% aspy		1	1	1	1	3
				At 189.76m slip at 60 deg to CA; At 189.8m - 189.89m aspy vn (90% aspy); med grained; increased cb alt'n						
10		190.00	190.90	High argillic alt'd GND; wi cb alt'n; aspy qtz-cb vn near base; 1 cm thick		2		4	2	
				Increased carbonate alt'n and veining						
10		190.90	191.80	GND wi multiple dark/more mafic "xenos" (again, perhaps potassic alt'd?); weakly chl alt'd xenos - BQAH? (60); relatively poor min'n		1	1	1	1	
80	191.8-218.67	191.80	192.90	Metasediments (hornfels?) - alternating btw BQAH (60) and QZZ (70); alternating btw dk brn (wi red tint) to light gy (QZZ); rare GND (191.53 - 191.58m); Common barren white quartz veins; contact @ 60 deg; At 191.58m-191.62m = irreg qtz vn; At 191.73m - 191.78m = Qtz vn at 80 deg; At 191.79 - 191.85m = Qtz vn at 80 deg						1
80		192.90	195.17	Silicified (bleached) metased with QZZ and Qtz veins; Qtz veins/vnlts generally barren or wi tr py		2				2
				selvage alt'n:				2		
80		195.17	196.35	Weakly alt'd though metam. Seds; 0.6mm leucocratic bands (qtz) wi thin bt lam; mnr qtz veining at 30 deg; GND "bleb" at base (196.3 - 196.35m)		1				1
80		196.35	198.12	Bleached metaseds; generally lt brown to off wht to grey (lt); multiple qtz vnlts to vns; mnr sulphides where cb present		4			1	3
				At 196.6m shear plane at 25%						
				197.5 - 197.58m Qtz vns - wht						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

PAGE 14 of 18

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)		Notes	CSV	Width (m)	VA05048596 Return Samples
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	0.6	4.0	30	40	1.0	ser/cb/arg	2		0.5			0.6									B292894	180.60	181.36	0.141			VA05049598	0.76	
3	1	0.6	2.0	30		0.5	ser/cb/arg	2		0.5			0.6									B292895	181.36	182.46	0.080			VA05049598	1.10	
																						B292896	BLANK		<0.005			VA05049598		
4	1	0.7	4.0	30		1.0	se/cb/arg	3		5.0			60.0									B292897	182.46	182.88	0.276		4 Quartz aspy vnlts; aspy up to 60%	VA05049598	0.42	
4	1	0.4	2.5	30	40	2.0	se/cb/arg	2		0.7			0.4									B292898	182.88	183.93	0.075			VA05049598	1.05	
5	1	1.5	4.0	30		10.0	ser/cb/arg	2		2.0			15.0									B292899	183.93	184.88	0.187			VA05049598	0.95	
1	1	1.5	1.5	30		10.0	ser/cb/arg	2		2.0			15.0										(184.14 | 184.16)			Qtz aspy vn = 15% aspy			
1	1	8.0	8.0	25	30	10.0	ser/cb/arg	3		4.0			12.0									B292900	184.88	185.06	0.922		Qtz py/aspy vn; c g py and aspy	VA05049598	0.18	
2	1	1.0	1.5	30		2.0	arg/se	2		1.0			0.5									B292901	185.06	186.37	0.563		Qtz-Aspy vnlt	VA05049598	1.31	
2	1	1.0	1.5	30		2.0	arg/se	2		1.0			0.5									B292902	185.06	186.37	0.724	DUP	Qtz-Aspy vnlt	VA05049598	1.31	
1	1	0.5	0.5	50		1.0	cb/arg/ser	3		3.0			11.0									B292903	186.37	187.04	0.182			VA05049598	0.67	
3	1	0.5	2.0	30		0.5	qtz/ser	2		2.0			1.0									B292904	187.04	187.45	0.165			VA05049598	0.41	
6	6	0.7	5.0	30	40	0.5	qtz/ser	2		4.0			80.0				0.5					B292905	187.45	188.98	0.643	*	Good sheeted qtz & aspy qtz vnlts	VA05049598	1.53	
3	1	1.0	4.0	30	40	1.0	qtz/ser	2		2.0			4.0									B292906	188.98	189.37	0.298			VA05049598	0.39	
2	6	0.9	1.5	60	40	1.0	qtz/cb/ser	2		4.0			80.0									B292907	189.37	190.00	3.220		0.9cm aspy vn	VA05049598	0.63	
2	6	0.8	1.5			10.0	cb/ser/arg	2		4.0			80.0									B292908	190.00	190.90	0.334		aspy vn (0.8cm)	VA05049598	0.90	
4	4	1.0	4.0			20.0	cb	4		0.8			0.5																	
4	4	1.0	4.0			20.0	cb	4		0.8			0.5									B292909	190.00	190.90	0.333	PD/CA		VA05049598	0.90	
																						B292910	STANDARD 5E		1.450	5E		VA05049598		
2	4	0.5	1.0	30	20	0.3	cb/se	1														B292911	190.90	191.80	0.140			VA05049598	0.90	
5	1	2.2	10.0	40																		B292912	191.80	192.90	0.139			VA05049598	1.10	
4	1	2.0	8.0	30																		B292913	192.90	193.80	0.179		Small Qtz-aspy-py veinlet	VA05049598	0.90	
1	1	0.3	0.3	35		1.0	qtz/ser/cb	2		3.0			20.0																	
7	1	2.0	12.0	30	25	2.0	qtz/ser/cb	2		0.4			0.2									B292914	193.80	195.17	0.082			VA05049598	1.37	
7	1	1.5	10.0	30	25	2.0	qtz/ser=	2		0.7			0.4									B292915	195.17	196.35	0.015			VA05049598	1.18	
																						B292916	BLANK		<0.005			VA05049598		
7	1	1.0	10.0	30	70	11.0	se/qtz	3		0.6			0.6									B292917	196.35	197.15	0.014			VA05049598	0.80	0.641
7	1	1.0	10.0	70	30	11.0	ser/qtz	3		0.5			0.5									B292918	197.15	198.12	<0.005			VA05049598	0.97	
1	1	8.0	8.0	70		11.0	ser/qtz	3		0.5			0.5										(197.5 | 197.58)						
3	4	0.4	2.0	40		0.5	cb/ser	1																						

DRILL HOLE # : DG05-282C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		198.12	202.76	Weakly alt'd metaseds; dk brn/grey; locly lt gy adj to some qtz vns; At 198.5m MSED foliation at 70 to 50 deg;		1				2
				Subtle fracture foliation at 140 deg relative to MSEDs and QV's						
				At 202.69m MSED foliation at 60 deg						
80		202.76	213.12	Weakly alt'd MSED (wi weak potassic alt'n?); local qtz-py +/- aspy veinlets; 202.76 - 203.2m fractured core; At 202.98 - 203.05m GND ser+arg+cb alt'd (2,2,3); parallel to MSED banding; At 204.7m MSED foliation at 70 deg to CA		2				1
				Vnlts at 160 - 140 deg relative to MSED; may be shr/fract derived						
				At 208.85 - MSED foliation at 70 deg; At 210.05m Qtz-Py vn at 150 deg relative to MSED						
				At 210.35 - 210.43m - Qtz vn (sample includes alt'd MSED wi 2-3% diss py/aspy)						
				At 210 m MSED at 65 deg with Qtz vning at 150 deg						
				At 210.97 - 211.02m = Shr/micro flt at 60 deg; ox'd and slightly gougy core; 211.36 - 211.46 QV at 80 deg						
80		213.12	213.86	MSED cont'd; relatively unalt'd; dk-med brown grey; few vns; At 213.50 fol'n at 80 deg		1				
80		213.86	218.67	MSED - mod'ly alt'd to med lt brn-grey due to qtz vns; locly wkly shr'd at 30 deg		3			1	
				At 215.18 m MSED fol'n at 55-60 deg; local K (bt) alt'n envelopes around qtz vnlts						
				Local relatively unalt'd zones bwtn 215.52-216.10m:		1			1	
				A few qtz/cb veins wi py/aspy; no min'n vis in selvage; x-cutting MSED fol'n; mnr shearing here; blebs of sph locally in qtz/cb vns						
				Moderate se-alt'n; large barren wht to slightly translucent QV's @ 217.10-217.43m; parallel to MSED fol'n at 50-60 deg						
10		218.67	221.62	Less alt'd GND; dk brn-gy; wk ser alt'n overall		1			1	
				At 221.45m MSED fol'n at 50 deg wi qtz vns/vnlts at 160-140 deg - barren		3			1	
80		221.62	228.86	Ser alt'd MSED; lt-med grn-gy, locally slightly sheared; Qtz vning wi tr-1% py; locally mod'ly silicified; MSED fol'n btw 50-70 deg wi both parallel and x-cutting Qtz vns; parallel vns generally thicker; local qtz-cb vns		1				
				Cross cutting vns locally with 1-3% py and sph						
				At 224.32m MSED slightly sheared to 40 deg wi cross-cutting fract fol'n at 120 deg; common parallel qtz vns wi locly tr-1% py						
				At 225.85m MSED foliation at 60 deg						
				At 227.24m MSED foliation at 57 deg						
80		228.86	230.73	Less alt'd (?) MSED; At 229.15m MSED at 60 deg wi local qtz vnlts at 150 deg (229.25m); At 230.70m MSED at 55 deg						
80		230.73	234.60	MSED; generally wkly to mod'ly alt'd and light grn-gy; locally low ser alt'n' wi dk brn-gy bt; loc qtz-cb fract filling (wk shr) x-cutting MSED fol'n at 155 deg; poorly min'd wi loc wht qtz		3			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2005

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA06048596 Return Samples
10	1	0.5	4.0	60		0.0																B292919	198.12	199.64	**0.012**			VA05049598	1.52	0.523
1	1	2.0	10.0	60	0																	B292920	199.64	201.17	**0.048**			VA05049598	1.53	0.684
																							(200.5 | 200.52)						
10	1	1.5	15.0	70	140	0.5	ser/qtz	1		0.3												B292921	201.17	202.76	**0.019**			VA05049598	1.59	0.468
																						B292922	201.17	202.76	**0.010**	DUP		VA05049598	1.59	
8	1	0.3	5.0	70	140	0.5	ser/qtz	1		1.5			1.0									B292923	202.76	203.20	**0.011**			VA05049598	0.44	0.36
11	1	0.8	10.0	160	70	0.4	ser/qtz	1		0.3												B292924	203.20	204.78	**0.01**			VA05052041	1.58	
3	6	0.5	2.0	160		0.2	qtz/ser	1		60.0			4.0									B292925	204.78	205.74	**1.655**			VA05052041	0.96	0.275
8	1	0.5	3.0	160	70	0.2	qtz/ser	1		0.5			0.4																	
3	1	0.5	2.0	160	140	0.5	qtz/ser	1		25.0			3.0				0.5					B292926	205.74	206.60	**0.109**			VA05052041	0.86	0.476
11	1	0.3	4.0	160		0.2	qtz/ser	1		0.3			0.3																	
8	1	0.3	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292927	206.60	207.26	**0.011**			VA05052041	0.66	
6	1	0.4	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292928	207.26	208.79	**0.013**			VA05052041	1.53	
6	1	0.4	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292929	207.26	208.79	**0.017**	PD/CA		VA05052041	1.53	
																						B292930	STANDARD 1A		**0.879**	1A		VA05052041		
4	1	0.2	3.0	160	70	0.2	qtz/ser	1		0.3			0.2									B292931	208.79	210.25	**0.014**			VA05052041	1.46	
1	1	8.0	0.8	140		1.0	q/ser	2		4.0			2.0									B292932	210.25	210.46	**0.846**		Qtz - py + aspy vn;	VA05052041	0.21	
4	1	0.3	2.0	140	70	0.5	qtz/ser	2		0.6			0.4									B292933	210.46	211.84	**0.015**			VA05052041	1.38	
10	1	10.0	16.0	140		0.4	ser/qtz	1		0.6			0.4									B292934	211.84	213.12	**0.009**			VA05052041	1.28	
1	1	10.0	10.0	80		1.0	ser/qtz	2															(212.36 | 212.46)						
2	6	0.2	0.3	35		1.0	ser/qtz	2		60.0			0.8									B292935	213.12	213.86	**<0.005**			VA05052041	0.74	
																						B292936	BLANK		**<0.005**			VA05052041		
6	1	1.2	4.0	150		10.0	qtz/ser	2		2.0			0.7									B292937	213.86	214.88	**0.009**			VA05052041	1.02	
3	1	2.2	4.0	50		0.3	qtz/ser	1		0.3			0.3									B292938	214.88	216.41	**0.009**			VA05052041	1.53	
4	1	0.2	1.0	150		0.6	k,ser	3		0.8			0.2																	
2	3	0.5	1.0	20	70	0.3	qtz/cb	1		0.3			0.3																	
3	3	1.0	4.0	165		1.0	cb/qtz	2		5.0			1.5									B292939	216.41	216.88	**0.023**			VA05052041	0.47	
2	1	1.0	2.0	70		0.2	qtz	2		0.3			0.3																	
3	1	16.0	20.0	50	60	11.0	se/qtz	3		0.2												B292940	216.88	217.93	**0.008**			VA05052041	1.05	
7	1	1.0	5.0	45		11.0	se/qtz	3		0.2												B292941	217.93	218.67	**<0.005**			VA05052041	0.74	
7	1	1.0	5.0	45		11.0	se/qtz	3		0.2												B292942	217.93	218.67	**<0.005**	DUP		VA05052041	0.74	
4	1	1.0	3.5	160		1.0	ser/qtz/cb	3		0.2												B292943	218.67	220.10	**0.017**			VA05052041	1.43	
3	1	0.8	2.5	140		0.8	k	3		0.2																				
4	1	0.8	3.0	140		2.0	ser/qtz/cb	3		0.2												B292944	220.10	221.62	**0.016**			VA05052041	1.52	
8	1	0.8	7.0	160		2.0	ser/qtz/cb	3		0.8			0.8									B292945	221.62	222.50	**0.042**			VA05052041	0.88	
4	1	0.6	3.0	160		0.5	ser/qtz	3		1.0			0.6									B292946	222.50	224.03	**0.019**			VA05052041	1.53	
2	4	0.5	1.0	160		1.0	ser/chl	3		0.5																				
2	1	0.8	2.0	160		1.0	ser/qtz	3		1.0			0.5		1.0															
6	1	0.5	3.0	40	50	1.0	ser/qtz	3		0.8												B292947	224.03	225.55	**0.026**			VA05052041	1.52	
5	1	0.4	3.0	60		1.0	ser	2		0.5												B292948	225.55	227.08	**0.007**			VA05052041	1.53	
10	1	0.3	5.0	140		0.3	ser	2		0.6																				
10	1	0.3	5.0	140		0.3	ser	2		0.6												B292949	225.55	227.08	**0.008**	PD/CA		VA05052041	1.53	
																						B292950	STANDARD 3C		**0.091**	3C		VA05052041		
5	1	0.5	4.0	60	162	0.3	ser/qtz	3		0.4												B292951	227.08	228.60	**0.016**			VA05052041	1.52	
2	1	0.3	0.6	130		0.1	ser/qtz	1		0.4												B292952	228.60	228.86	**0.006**			VA05052041	0.26	
3	1	0.5	2.0	150		0.5	ser/qtz	2		0.4												B292953	228.86	230.12	**0.006**			VA05052041	1.26	
3	1	0.4	2.0	140		1.0	ser	1	1													B292954	230.12	230.73	**<0.005**			VA05052041	0.61	
4	1	0.5	4.0	130		2.0	ser/cb	3		0.5												B292955	230.73	231.88	**<0.005**			VA05052041	1.15	
																						B292956	BLANK		**<0.005**			VA05052041		
4	1	2.0	4.0	130		3.0	ser	3		0.5												B292957	231.88	233.17	**<0.005**			VA05052041	1.29	

DRILL LOG LEGEND P1	DATE: June 14-17, 2005	PAGE 17 of 18	
DRILL HOLE # : DG05-282C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		234.60	237.80	Increasing alt'n and shr (?); Rock softer; irregular to shr are dk py vns; increase wht qtz vns; lost competency; nearing a lower contact with GND dike; 235.4 - 235.41m Flt-shr gg at 165 deg to CA		3		2	2	
				At 237.44 - 237.47m Py-qtz vn wi 70% py, broken core; possibly highly arg alt'd GND (2X 3-5cm intervals, broken core)						
10	237.8-240.53	237.80	240.53	GND - Highly argillic-ser-+/- cb alt'd, lt gm-gy, appears wkly sheared wi arg/clay fract filling; no vis bt; local py fract filling (dk gy - black)		4		3	3	
				Possibly shr related vnlts - 80% py						
				Moderately hard dk brn mineral in py-qtz vn, no sph						
80	240.53-251.46	240.53	245.53	MSED; Upper contact somewhat irreg at 65 deg; mod'ly alt'd (ser); competent; pyritic shr vns in upper sample; at 28 deg to CA; at 90 deg to fol'n (70 deg); multiple py +/- cpy +/- aspy bearing vns in first 3m		3				1
				Irregular py/cpy/aspy stringer zone; appears to be intrusive, with small frags of MSED in sulphide mtx; moderately silicified; similar to prev though less min'n						
				No vis py stringers; multiple off wht qtz vns						
				Aspy + qtz + py vn at 150 deg relative to MSED fol'n at 50 deg; similar to sulphide veins in previous samples						
80		245.53	251.46	Relatively unaltered (hornfels?) MSED; MSED common foliation parallels qtz vns (pre-metam) at 50 deg with x-cutting qtz vns at 150 deg; At 246.54m MSED fol'n at 50 deg		1				
				MSED; dk brn gry at 50 deg to CA						
				MSED foliation at 80 deg at 248.9m						
				GND (mod arg/ser alt'd) at 250.21 - 250.3m and 250.57 - 250.63m; increasing se alt'n at EOH, no vis min'n						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 14-17, 2006

LOGGED BY: D. Hladky & K. Whitehead

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																							
						Selvages				Sulphides										Oxidation						Interval								
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)		Notes	CSV	Width (m)	VA05048596 Return Samples
4	1	3.0	5.0	140		10.0	ser/cb/arg	3		0.5												B292958	233.17	234.60	**0.028**			VA05052041	1.43	
3	1	1.5	2.0	140		2.0	ser/cb/arg	3		25.0			0.8									B292959	234.60	235.58	**0.933**			VA05052041	0.98	
4	6	0.2	0.6	160		1.0	ser/arg/cb	3		60.0			1.0																		
5	1	0.7	4.0	60	70	3.0	ser/cb/arg	3		0.5												B292960	235.58	236.55	**0.026**			VA05052041	0.97	
7	1	0.7	6.0	60		3.0	ser	3		1.0												B292961	236.55	237.80	**0.094**			VA05052041	1.25	
1	6	2.5	2.5	60		3.0	qtz/ser	3		70.0			4.0																		
7	1	0.7	6.0	60		3.0	ser	3		1.0												B292962	236.55	237.80	**0.082**	DUP		VA05052041	1.25	
1	6	2.5	2.5	60		3.0	qtz/ser	3		70.0			4.0																		
10	1	2.0	8.0	70	160	10.0	arg/ser/cb	4		3.0			0.8									B292963	237.80	239.27	**0.011**			VA05052041	1.47	
3	6	0.1	1.0	70	160	0.5	arg/ser/cb	4		70.0			0.8																		
7	1	3.0	10.0	60		11.0	arg/ser/cb	4		3.0			1.0									B292964	239.27	240.79	**0.061**			VA05052041	1.52	
3	6	0.3	2.0	170		0.1	arg	4		80.0			1.0																		
5	1	0.8	3.0	60	70	10.0	arg/ser/cb	3		2.0			0.8									B292965	240.79	241.53	**0.066**			VA05052041	0.74	
1	6	0.5	0.5	50		1.0	ser/ch	3		3.0			3.0								5.0										
3	6	0.8	3.0	25		2.0	qtz/ser	3		55.0												B292966	241.53	242.16	**0.358**			VA05052041	0.63	
5	1	0.7	3.0	60		3.0	qtz/ser	3		0.6												B292967	242.16	243.10	**0.051**			VA05052041	0.94	0.548
3	6	3.0	6.0	30	40	5.0	qtz	3		25.0		15.0	20.0									B292968	243.10	243.54	**2.46**			VA05052041	0.44	
3	6	3.0	6.0	30	40	5.0	qtz	3		25.0		15.0	20.0									B292969	243.10	243.54	**2.45**	PD/CA	High Sulphides	VA05052041	0.44	
																						B292970	STANDARD 7G		**4.63**	7G		VA05052041		
3	6	0.3	1.2	40		4.0	qtz	3		20.0		2.0	5.0									B292971	243.54	243.84	**0.254**			VA05052041	0.30	
5	1	9.0	15.0	70		5.0	qtz/ser	3		0.8												B292972	243.84	244.60	**0.092**			VA05052041	0.76	
1	6	3.0	3.0	150		3.0	qtz	3		8.0			12.0									B292973	244.60	244.75	**1.055**			VA05052041	0.15	
7	1	0.5	3.0	150		0.5	qtz/ser	3		1.0												B292974	244.75	245.53	**0.067**			VA05052041	0.78	
8	1	1.0	6.5	150		0.3	qtz/ser	3		0.5												B292975	245.53	246.89	**0.008**			VA05052041	1.36	0.687
10	1	1.0	6.0	50																											
																						B292976	BLANK		**<0.005**			VA05052041		
5	1	0.7	4.0	137	140	1.0	ser	2		0.5												B292977	246.89	248.41	**0.014**			VA05052041	1.52	0.877
1	1	6.0	6.0	137		1.0	ser	2		6.0			1.0										(247.10	247.16)							
6	1	1.0	5.0	160		2.0	ser	2		0.5			0.2									B292978	248.41	249.94	**0.009**			VA05052041	1.53	0.836
1	1	10.0	10.0	80		0.5	ser	1		0.5													(249.4	249.5)							
5	1	3.0	6.0	80		10.0	ser	2		0.5												B292979	249.94	251.46	**<0.005**			VA05052041	1.52	0.755
2	1	0.5	1.0	155		1.0	ser/cb	3		0.5																					0.661
																						EOH									

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-283C

PROJECT: Dublin Gulch

GROUND ELEVATION: 998m

BEARING: 000 | DIP: -50°

DATE STARTED: 12-Jun-05 | DATE COMPLETED: 15-Jun-05

COORD SYSTEM: NAD 27: EASTING: 459704 NORTHING: 7099087

COORD SYSTEM: NAD 83: EASTING: 459585 NORTHING: 7099271

NAD 27 (CORRECTED for historic grid): EASTING: 459674 NORTHING: 7099097

LOGGED BY: M. Stone

SECTION LINE(historic grid): 459674E

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: to 22.86m

Deviation:

Casing: 22.86m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
21.34	205.74	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B292034 to 292174

Requisition #: MASP448STRGOL.05Q | Date Shipped: 14-June-05

Lab Record #: VA05049843 | Date Received: 23-June-05

Sample Sequence: B292175 - B292214

Requisition #: MASP448STRGOL.05Q | Date Shipped: 21-June-05

Lab Record #: VA05051469 | Date Received: 29-June-05

Duplicates:	B292042, B292062, B292082, B292102, B292122, B292142, B292162, B292182, B292202
Preparation Duplicate/ Check Assay:	B292049, B292069, B292089, B292109, B292129, B292149, B292169, B292189, B292209
Standards:	B292050, B292070, B292090, B292110, B292130, B292150, B292170, B292190, B292210
Blanks:	B292036, B292056, B292076, B292096, 292116, B292136, B292156, B292176, B292196

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	340.5	50.2	6.5	7.5
150	341.2	49.5	7.2	8.2
205.74	342.5	48.1	8.5	9.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 1 of 14			
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 21.34			Casing (no recovery)						
10	21.34-205.76m	21.34	22.86	Extremely altered GND. Competent chunks up to 3cm diameter, oxidized through. sericite clay and argillic clay make up 80% of sample	5	4	2	4		
10		22.86	25.91	Extremely altered but coherent rock. purple hue suggests hematite content (up to 40%) Carbonate on veinlets close to parallel w/ C.A. Qtz eyes visible, remnant GND texture barely. sand size gouge section @ 23.6m (10cm wide)	5	4	2	1	1	
10		25.91	28.00	Oxidized GND. Colour light to med brown. 3cm gouge (clay) section with slickensides (mod strength) at 26.5m. Yellowish brown clay	5	3	2	1		
10		28.00	28.96	Same rock, but more clay alteration (30%). Highly altered and broken up GND. Breakage at parallel to CA - 10°	5	4	2	1	1	
10		28.96	31.29	Same as 25.91 to 28.00m, except gouge @ 29.85 (cm wide)	5	4	2	1	1	
10		31.29	32.00	May have once been one large qtz vein, chunky qtz pieces up to 4cm wide dominate the section. Gouge (clay to sand) section from 31.8 - 32.00	5	4	1	2		
10		32.00	34.05	Med to light brown GND. Original texture 90% overprinted and aphanitic	5	4	3	2		
10		34.05	35.05	Poor recovery here. Deep brown sandy alteration product makes rock very crumbly	4	2	3	1	1	
10		35.05	36.20	Extremely altered, but coherent rock. Veinlets show lim/calcite. Overall colour greyish dark brown w/ green (CHL) and orange (LIM) on veinlets w/ wide, pervasive selvages	4	2	3	1	1	
10		36.20	37.00	Poor recovery, same rock. Veinlets are everywhere, approach 20 per $10cm^2$	5	2	1	2		
10		37.00	38.10	Oxidized (limonized) selvage around qtz veins and lim veinlets separated by unaltered GND (up to 8cm across, uneven patches).	3	1	1			
10		38.10	42.67	Extremely altered GND. Gouge to crumbly gravel section. Competent zones (still highly oxidized), up to 8cm long	4	2	3	3	1	
10		42.67	44.25	Brown, coherent GND (as at 35.05 - 36.20m but w/ less chl) vein full of hematite, red, concretionary texture	4	2	1	2	1	
10		44.25	47.24	Altered to clay (appears as gouge, but no slickensides). and minor brecciated GND	4		1	4	1	
10		47.24	49.54	V. broken up core. Pieces avg 4cm. Lim staining pervasive. hematite w/in qtz veins and at margins to 15%	4	1	1	1	1	
10		49.54	50.44	Broken up, limonized rock, w/ minor clay	4		1	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
0																						B292034	21.34	22.86	**0.134**			VA050549843	1.52
0																						B292035	22.86	24.38	**0.052**			VA050549843	1.52
																						B292036	BLANK		**0.006**			VA050549843	
																						B292037	24.38	25.91	**0.034**			VA050549843	1.53
2	1	0.5	0.8	10	30		s	2	5	1.0								5.0				B292038	25.91	27.43	**0.036**			VA050549843	1.52
							q	4																					
1	1	0.5	0.5	20			s	2	5													B292039	27.43	28.00	**0.021**			VA050549843	0.57
							q	4																					
1	4	0.3	0.3				cb	3	5													B292040	28.00	28.96	**0.066**			VA050549843	0.96
3	1	0.5	1.2	60	30		s	3	5	0.1								1.0				B292041	28.96	30.48	**0.091**			VA050549843	1.52
							q	3																					
3	1	0.5	1.2	60	30		s	3	5	0.1								1.0				B292042	28.96	30.48	**0.06**	DUP		VA050549843	1.52
							q	3																					
4	1	1.0	3.0	60			q	3	5													B292043	30.48	31.29	**0.099**			VA050549843	0.81
1	1	20.0	20.0				q	3	5	7.0		0.1						5.0				B292044	31.29	32.00	**0.702**		Qtz pieces	VA050549843	0.71
							s	5																					
1	6	1.0	1.0	50						100.0								4.0											
2	1	0.5	0.8	60						1.0								4.0				B292045	32.00	33.53	**0.022**			VA050549843	1.53
4	1	0.5	2.0	80	45		chl	1		1.0								5.0				B292046	33.53	34.05	**0.863**			VA050549843	0.52
							q	4																					
							s	4																					-
0																						B292047	34.05	35.05	**0.103**			VA050549843	1.00
5	1	1.0	3.5	60	50		s	4	5	4.0			3.0					4.0	4.0			B292048	35.05	36.20	**0.059**			VA050549843	1.15
							chl	2																					
							q	2																					
5	1	1.0	3.5	60	50		s	4	5	4.0			3.0					4.0	4.0			B292049	35.05	36.20	**0.056**	PD/CA		VA050549843	1.15
							chl	2																					
							q	2																					
																						B292050	STANDARD 7G		**4.7**	7G		VA050549843	
2	1	0.4	0.8	50			s	4	5	0.0												B292051	36.20	37.00	**0.035**			VA050549843	0.80
							chl	2																					
							q	2																					
4	1	1.0	3.0	50	65		s	4	5	2.0								5.0				B292052	37.00	38.10	**0.028**			VA050549843	1.10
							chl	2																					
							q	2																					
0																						B292053	38.10	39.62	**0.118**			VA050549843	1.52
2	1	0.3	0.6				s	4	5													B292054	39.62	41.15	**0.05**			VA050549843	1.53
							chl	2																					
							q	2																					
3	1	0.5	1.0	30	10		s	4	5	1.0								5.0				B292055	41.15	42.67	**0.212**			VA050549843	1.52
							chl	2																					
							q	2																					
1	4	0.5	0.5	30		0.5	cb	2		1.0								5.0											
							chl	1																					
																						B292056	BLANK		**<0.005**			VA050549843	
0																						B292057	42.67	43.47	**0.043**			VA050549843	0.80
0																						B292058	43.47	44.25	**0.026**			VA050549843	0.78
0																						B292059	44.25	45.52	**0.007**			VA050549843	1.27
0																						B292060	45.52	47.24	**0.12**			VA050549843	1.72
1	4	3.0	3.0	30			cb	2														B292061	47.24	48.77	**0.04**			VA050549843	1.53
							s	3																					
							chl	1																					
1	4	3.0	3.0	30			cb	2														B292062	47.24	48.77	**0.034**	DUP		VA050549843	1.53
							s	3																					
							chl	1																					
1	1	1.3	1.3	25			q	2		5.0			1.0					5.0				B292063	48.77	49.54	**0.057**			VA050549843	0.77
							s	3																					
							chl	1																					
2	1	1.1	2.2				q	2		3.0								5.0				B292064	49.54	50.44	**0.013**			VA050549843	0.90
							s	3																					

DRILL LOG LEGEND P1			DATE: June 11-16th, 2005 PAGE 3 of 14								
DRILL HOLE # : DG05-283C			FeOx: 0 = Unoxidized, 5 = Intensely Ox'd; Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered						Carbonate: 0 = No Effervescence, 5 = Strong Effervescence		
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93											
	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
UNIT CODE	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
10		50.44	53.34	V broken up core w/ limonite and calcite on fracture faces and limonite pervasive. Slickensides (med grade) on fracture face to 40° to CA, shown in sericite	4	1	1	1	2		
10		53.34	54.44	Area of granular GND w/ alt'n zones separated by unaltered zones up to 8cm in diameter. Massive aspy vein w/in qtz vein	2	1	1	1	1		
10		54.44	54.74	Clay zone. No evidence of fault or shear here, but upper and lower to it has slickensides. Limonite and carbonate clay.	5	1	1	4	3		
10		54.74	55.97	Lim/carb rich altered GND. Coherent, relict GND texture easily visible in qtz/bt, but overall, colour is yellowish brown. Qtz vein broken but still in situ in coherent core.	3		1	1	3		
10		55.97	57.91	Less alt'd here. Unaltered GND between selvages around veinlets of limonite	3		1		3		
10		57.91	60.96	Slickensides in oxidized py and sericite. Strong on fracture faces @ 45° and 30°. Moderate altered GND							
10		60.96	65.53	Unaltered GND (20%) separated by selvages of veinlets of lim/calcite (mod slickensides) and sulphide veins. Slickensides in ox. py. on fracture faces @ 45° and 30°, sand size and crumbly texture for 20% of section							
10		65.53	70.10	Lim-alt'd GND w/ calcite. Color is pale brown. Relict texture of GND (90%). Vnlets w/ lim/calc are random & irregular.	3	0	1	1	2		
10		70.10	71.20	Grades from lim-stained GND relict texture to completely alt'd & unrecognizable w/ qtz, chunky w/ vnlets of ox'd py, ~5% of sample.	4	1	1	1	2		
10		71.20	71.63	Clay/gravel texture. Lenses of black, alt'd bt.							
10		71.63	83.13	GND, highly alt'd to crumbly, mostly (80%) incompetent rocks. Lim & calc vnlets pervade the rock & weaken it. Overall color white, orange & brown. Black bt speckles. Vns exist as alt'd/broken lines of qtz chunks: rounded; associated w/ clay-like black lenses of ox'd py.	4	1	1	3	4		
10		83.13	87.80	Clean, unalt'd GND except for selvages around grey qtz vns & minor sericite throughout GND for part.	1	2	0	0	1		
10		87.80	100.58	Rock dominated by lim staining & calcitic selvage. GND texture relict beneath brown staining. Small unalt'd sections (<10cm) where vnlets are less frequent (only 8 per 10cm of core). Most sections vnlets >20/cm. Crumbly/sandy texture (50%), broken up core to pc's <10cm (50%). at 93-93.1m: a qtz-carb vn.	3	2	1	2	3		

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	1																					
1	4	0.4	0.4	40																		B292065	50.44	51.82	**0.023**			VA050549843	1.38
1	1	2.0	2.0			10.0	q	4	5	5.0			1.0					5.0	3.0			B292066	51.82	53.34	**0.015**		Qtz pieces	VA050549843	1.52
							s	2																					
1	6	1.0	1.0	20		4.0	q	3					40.0									B292067	53.34	54.44	**0.18**			VA050549843	1.10
0																						B292068	54.44	54.74	**0.028**			VA050549843	0.30
0																						B292069	54.44	54.74	**0.029**	PD/CA		VA050549843	0.30
																						B292070	STANDARD 5E		**1.435**	5E		VA050549843	
1	3	0.6	0.6	30		1.0	q	2	4	2.0			15.0					4.0	1.0			B292071	54.74	55.97	**0.097**			VA050549843	1.23
							cb	2																					
1	1	1.0	1.0	20		4.0	q	3	4				0.1																
0																						B292072	55.97	56.59	**0.098**			VA050549843	0.62
0																						B292073	56.59	57.91	**0.057**			VA050549843	1.32
0																						B292074	57.91	59.44	**0.073**			VA050549843	1.53
2	6	2.0	4.0	60		4.0	q	3	1	5.0			1.0					4.0				B292075	59.44	60.96	**0.061**			VA050549843	1.52
							cb	2																					
																						B292076	BLANK		**<0.005**			VA050549843	
1	1	1.0	1.0	40		3.0	q	4		10.0			5.0					4.0				B292077	60.96	62.48	**0.064**			VA050549843	1.52
							s	2																					
1	1	0.5	0.5							5.0								5.0				B292078	62.48	63.00	**0.068**		Qtz piece	VA050549843	0.52
1	1	0.5	0.5	30		1.0	q	4	3													B292079	63.00	64.01	**0.021**			VA050549843	1.01
							s	2																					
4	1	0.5	2.0	40	50	4.0	q	4	4		5.0							5.0				B292080	64.01	65.53	**0.177**			VA050549843	1.52
							s	2																					
3	1	0.5	1.5	50		1.4	q	4		2.0			1.0					4.0	5.0			B292081	65.53	67.06	**0.193**			VA050549843	1.53
							cb	4																					
1	6	1.0	1.0	50									80.0						1.0										
3	1	0.5	1.5	50		1.4	q	4		2.0			1.0					4.0	5.0			B292082	65.53	67.06	**0.191**	DUP		VA050549843	1.53
							cb	4																					
1	6	1.0	1.0	50									80.0																
1	1	0.4	0.4	50		52.0				5.0								5.0				B292083	67.06	68.58	**0.046**		Selvage is entire sample	VA050549843	1.52
4	1	0.5	2.0	30		2.0	q	3	1	5.0								5.0				B292084	68.58	70.10	**0.162**			VA050549843	1.52
							cb	2																					
										5.0								5.0				B292085	70.10	71.20	**0.132**			VA050549843	1.10
0																						B292086	71.20	71.53	**0.476**			VA050549843	0.33
2	1	1.0	2.0	60						5.0								5.0				B292087	71.53	73.00	**0.19**			VA050549843	1.47
1	1	2.0	2.0							5.0								5.0				B292088	73.00	73.74	**0.218**			VA050549843	0.74
1	1	2.0	2.0							5.0								5.0				B292089	73.00	73.74	**0.226**	PD/CA		VA050549843	0.74
																						B292090	STANDARD 1A		**0.771**	1A		VA050549843	
2	1	1.0	2.0	70						5.0												B292091	73.74	74.68	**1.35**			VA050549843	0.94
0																						B292092	74.68	76.20	**0.088**			VA050549843	1.52
0																						B292093	76.20	77.72	**0.143**			VA050549843	1.52
3	1	1.2	3.2	35	50					0.1								5.0				B292094	77.72	79.26	**0.068**			VA050549843	1.54
1	1	1.0	1.0							1.0								5.0				B292095	79.26	80.77	**0.203**			VA050549843	1.51
																						B292096	BLANK		**<0.005**			VA050549843	
2	3	2.0	3.0	55						0.1								5.0				B292097	80.77	82.30	**0.069**			VA050549843	1.53
3	1	3.0	5.5	55						10.0								5.0				B292098	82.30	83.13	**0.047**			VA050549843	0.83
3	1	1.5	3.0	40		2.0	q	3			10.0							2.0				B292099	83.13	83.82	**0.036**			VA050549843	0.69
							s	3																					
4	1	2.3	5.1	40		4.5	q	3		1.0	10.0		3.0					1.0	4.0			B292100	83.82	85.34	**0.299**			VA050549843	1.52
							s	3																					
3	1	1.0	3.0	40		3.0	q	3		2.0	1.0		1.0					4.0	3.0			B292101	85.34	86.87	**0.222**			VA050549843	1.53
							s	3																					
3	1	1.0	3.0	40		3.0	q	3		2.0	1.0		1.0					4.0	3.0			B292102	85.34	86.87	**0.198**	DUP		VA050549843	1.53
							s	3																					
0																						B292103	86.87	87.80	**0.014**			VA050549843	0.93
0																													
2	1	1.0	2.0	40			s	2	4	0.1								3.0				B292104	87.80	88.39	**0.039**			VA050549843	0.59

DRILL LOG LEGEND P1	DATE: June 11-16th, 2006 PAGE 5 of 14	
DRILL HOLE # : DG05-283C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd; Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		100.58	102.65	V. broken, unalt'd GND broken on lim microfracs at reg angles to CA: 40°/120°. Carbonitized section from 102.01-102.11m, w/ slickensides & a sheared-out appearance, trending to 60° to CA. V. white (sericite, carb) w/ slickensides defined in vnlet of mafics (alt bt?).	1	1	0	1	1	
10		102.65	103.63	V. broken core, lim near pervasive but ~2-5cm pc's, unalt'd in the centre.	2	2	0	1	1	
10		103.63	109.73	Carbonitized/sericitized GND. Selvages noted are in immediate proximity, if available. Carbonate appears in vns as well as throughout matrix of GND.	0	4	0	1	3	
10		109.73	112.78	Carb-ser alt'n to pervasive crumbly clay rich rock. Light grey-white shear zone. Slickensides (ser & alt bt) & aligned planar sericite throughout. Mafic lenses are dark grey clay & make up 50% of section; does not include py - too soft; none visible shear zone hits competent rock @ 50° to CA. No limonite.	0	4	0	4	3	
10		112.78	121.92	Minor alt'd GND. Slightly silicified & sericitized & carbonitized. GND texture for 90% of section where alt'n is, rock is more crumbly & white. V. minor limonite on 5% of section (end 1m). 4x3cm xenolith (mafic) f. grained diorite @ 115.70m few more ~1cm diameter throughout section (3). 2cm shear section combining pale beige gouge sand. Evidence of shear in mafic (dark grey clay) bands, movement appears to 90° to CA.	0	2	0	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							q	2														B292105	88.39	89.92	**0.044**			VA050549843	1.53
3	1	2.0	4.0	50						1.0			5.0					5.0	3.0			B292106	89.92	91.44	**0.226**			VA050549843	1.52
2	1	1.5	2.5	50		2.0	q	2					4.0					1.0				B292107	91.44	92.71	**0.478**			VA050549843	1.27
							chl	1																				
							s	1																				
1	4	2.0		20		8.0	s	3	3	10.0								5.0				B292108	92.71	93.18	**0.164**			VA050549843	0.47
							q	2																				
							cb	3																				
1	4	2.0		20		8.0	s	3	3	10.0								5.0				B292109	92.71	93.18	**0.171**	PD/CA		VA050549843	0.47
							q	2																				
							cb	3																				
																						B292110	STANDARD 6F		**3.07**	6F		VA050549843	
3	1	2.0	5.0	40		3.0	q	3			5.0							4.0				B292111	93.18	94.49	**2.6**			VA050549843	1.31
							s	1																				
1	1	1.0	1.0	10		2.0	q	3	3				5.0						1.0			B292112	94.49	96.01	**0.438**			VA050549843	1.52
							s	3																				
1	1	1.0	1.0	30		2.0	q	4	3				2.0						1.0			B292113	96.01	97.54	**0.162**			VA050549843	1.53
							s	2																				
0																						B292114	97.54	99.06	**0.144**			VA050549843	1.52
3	1	0.5	1.5	45		2.0	q	4	1	7.0	1.0		5.0					4.0	5.0			B292115	99.06	100.58	**0.324**			VA050549843	1.52
							s	3																				
																						B292116	BLANK		**<0.005**			VA050549843	
3	1	0.5	1.5	45		1.0	q	3	1		5.0		1.0						3.0			B292117	100.58	102.11	**0.092**			VA050549843	1.53
							s	3																				
2	6	0.4	0.6	50	140	2.0	q	2		2.0	65.0	2.0						5.0				B292118	102.11	102.65	**0.116**			VA050549843	0.54
							s	1																				
2	1	2.0	4.0				q	2	4	1.0								5.0				B292119	102.65	103.63	**0.109**			VA050549843	0.98
							s	3																				
3	4	4.0	10.0	45		5.0	s	4			0.1		1.0						2.0			B292120	103.63	105.16	**0.069**			VA050549843	1.53
							cb	4																				
5	1	3.0	5.1	30		2.0	q	1		1.0	3.0							4.0				B292121	105.16	106.68	**0.152**			VA050549843	1.52
							chl	3																				
							s	3																				
5	1	3.0	5.1	30		2.0	q	1		1.0	3.0							4.0				B292122	105.16	106.68	**0.094**	DUP		VA050549843	1.52
							chl	3																				
							s	3																				
1	4	2.0	2.0	40																		B292123	106.68	108.20	**0.156**			VA050549843	1.52
3	1	2.0	5.0	70		3.0	q	3																					
							s	3																				
3	1	2.0	5.0	50		2.0	q	4		5.0								5.0				B292124	108.20	109.73	**0.134**			VA050549843	1.53
							s	3																				
																						B292125	109.73	111.25	**0.156**			VA050549843	1.52
																						B292126	111.25	112.78	**0.096**			VA050549843	1.53
3	1	1.0	2.5	30	45	1.0	q	3			8.0		2.0					1.0				B292127	112.78	114.30	**0.024**			VA050549843	1.52
											s	3.0																	
4	1	1.0	3.5	45		2.0	q	3		2.0	12.0	0.1						2.0				B292128	114.30	115.82	**0.017**			VA050549843	1.52
							s	1																				
1	2	1.5	1.5	25		0.5	q	2																					
4	1	1.0	3.5	45		2.0	q	3		2.0	12.0	0.1						2.0				B292129	114.30	115.82	**0.018**	PD/CA		VA050549843	1.52
							s	1																				
1	2	1.5	1.5	25		0.5	q	2																					
																						B292130	STANDARD 7G		**4.15**	7G		VA050549843	
2	1	0.4	0.8	25																		B292131	115.82	117.35	**0.07**			VA050549843	1.53
1	1	1.0	1.0	60		1.0	q	1			5.0																		
1	1	1.0	1.0	40		1.0	q	1			2.0											B292132	117.35	118.87	**0.028**			VA050549843	1.52
							s	1																				
2	1	1.0	2.0	40		0.5	q	1			1.0							2.0				B292133	118.87	120.40	**0.009**			VA050549843	1.53
							s	1																				
2	1	1.0	2.0	50		1.0	q	1		1.0	5.0							2.0				B292134	120.40	121.92	**0.038**			VA050549843	1.52

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 7 of 14	
DRILL HOLE # : DG05-283C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		121.92	135.64	V. minor alt'd GND. Slightly more mafic in appearance. Vnlets, infrequent, of calcite infrequent 1 or 2/m of qtz w/ po. no (<1%) limonite. small xeno @ 124.5m, long axis parallel to qtz vn (40° to CA). 3x1cm. Reg breakage @ 30 & 80° to CA. Mod mineral slickensides on 30° faces, bt or dark sericite (soft, micaceous). 90% of qtz vns are grey qtz in the centre, w/ silicified zones surrounding. @ 133.6-135.64m: parallel to CA fracs break core lengthwise (2, mainly).	0	1	0	0	1	
10		135.64	139.59	Minor alt'd GND. Selvages around fracs & xenoliths account for alt'n. Slickensides in sericite/chlorite on frac faces @60° to CA.	0	1	1	0	0	
10		139.59	147.51	V. minor alt'd GND (carb), w/ large qtz vns (8cm max), small selvages. Xeno's up to 15x8cm (@142.2m) in size.	0	1	1	0	1	
				Cube ($1cm^2$) of qtz surrounded by 4mm selvage of chlorite @141.9m.						
				At 144.38m, nice, 1-2mm cpy. Slickensides on fractures @20-40° to CA increase in strength toward end of sample						
10		147.51	148.20	Fault zone. Crumbly gouge to gravel (brecciated GND). Contacts unalt'd GND at 20° (upper) & 35° (lower) w/ nice sericite slickensides.	1	3	2	3	3	
10		148.20	151.69	Carbonitized GND. Calcite in vnlets & through matrix of GND, making its texture crumbly & granular. Overall, color is whitish pale grey.	1	2	1	0	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							s	1																					
4	1	1.0	4.0	30	45	1.5	s	3		1.0	9.0							2.0				B292135	121.92	123.44	**0.012**			VA050549843	1.52
							q	3																					
																						B292136	BLANK		**<0.005**			VA050549843	
6	1	0.5	3.0	40		0.5	q	3		2.0			1.0									B292137	123.44	124.97	**0.046**			VA050549843	1.53
							s	3																					
5	1	1.0	5.0	45			q	3		2.0			1.0									B292138	124.97	126.49	**0.06**			VA050549843	1.52
							s	3																					
4	1	2.0	4.0	30	40	3.0	q	3			5.0		4.0					3.0	1.0			B292139	126.49	128.02	**0.011**			VA050549843	1.53
							s	2																					
							chl	2																					
0																						B292140	128.02	129.54	**0.057**			VA050549843	1.52
2	1	0.4	0.8	80	30	1.0	q	3			2.0							4.0				B292141	129.54	131.06	**0.012**			VA050549843	1.52
							s	2																					
2	1	0.4	0.8	80	30	1.0	q	3			2.0							4.0				B292142	129.54	131.06	**0.026**	DUP		VA050549843	1.52
							s	2																					
5	1	1.0	4.0	40		1.0	q	4			8.0							2.0				B292143	131.06	132.59	**0.066**			VA050549843	1.53
							s	2																					
0																						B292144	132.59	134.11	**0.006**			VA050549843	1.52
2	1	2.0	3.0	40	50	1.5	q	3			8.0		3.0					1.0	5.0			B292145	134.11	135.64	**0.018**			VA050549843	1.53
							s	3																					
5	1	2.3	5.0	40	50	1.0	q	3	0	0.1	3.0		4.0					5.0	4.0			B292146	135.64	137.16	**0.088**			VA050549843	1.52
							chl	1																					
							s	1																					
5	1	0.5	2.5	45		1.5	q	4			1.0		10.0						4.0			B292147	137.16	138.68	**0.04**			VA050549843	1.52
							chl	1																					
							s	2																					
1	1	0.5	0.5	40		2.0	q	2		10.0								2.0				B292148	138.68	139.59	**0.02**			VA050549843	0.91
							chl	3																					
							s	2																					
1	1	0.5	0.5	40		2.0	q	2		10.0								2.0				B292149	138.68	139.59	**0.021**	PD/CA		VA050549843	0.91
							chl	3																					
							s	2																					
																						B292150	STANDARD 3C		**0.082**	3C		VA050549843	
2	1	1.0	2.0	40		1.0	q	2		5.0								1.0				B292151	139.59	140.21	**0.093**			VA050549843	0.62
							chl	3																					
							s	2																					
4	1	1.3	4.0	40		2.0	q	4		5.0								2.0				B292152	140.21	141.73	**0.012**			VA050549843	1.52
							chl	1																					
							s	1																					
2	1	1.0	1.5	20	30	4.0	q	5	0	1.0								5.0				B292153	141.73	143.26	**0.013**			VA050549843	1.53
3	1	3.0	5.0	45		6.0	q	3	1		10.0	2.0						2.0				B292154	143.26	144.78	**0.162**			VA050549843	1.52
							chl	3																					
							s	2																					
2	1	6.0	8.0	20		2.0	q	3	0		10.0							2.0				B292155	144.78	146.30	**0.043**			VA050549843	1.52
							chl	3																					
							s	2																					
																						B292156	BLANK		**<0.005**			VA050549843	
2	1	1.0	2.0	30	10	4.0	q	3	0		8.0		4.0					2.0	2.0			B292157	146.30	147.51	**0.108**			VA050549843	1.21
							chl	3																					
							s	2																					
0																						B292158	147.51	148.20	**0.022**			VA050549843	0.69
3	3	2.5	6.5	20	30	5.0	q	3	1		5.0		3.0					1.0	3.0			B292159	148.20	148.87	**0.08**			VA050549843	0.67
							cb	3																					
							s	3																					
1	1	1.3	1.3	50		4.0	q	3			2.0		2.0					0.0	0.0										
							chl	3																					
							s	2																					
0																						B292160	148.87	149.35	**0.028**			VA050549843	0.48
4	1	2.0	4.5	50		6.0	q	3			15.0		1.0					1.0	3.0			B292161	149.35	150.88	**0.045**			VA050549843	1.53
							chl	3																					

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005	PAGE 9 of 14	
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		151.69	154.68	Mod'ly alt'd GND. Calcite-infused from vnlets & through matrix.	0	3	2	0	2	
10		154.58	156.74	Carb & chl & ser-alt'd GND. Crumbly gravel to sandy texture. GND texture 90% erased. Weak slickensides on irregular frac faces, in alt'd bt & ox'd py. General trend to these black lenses is 45° to CA. Color is minty green w/ grey & white patches.	0	4	3	1	3	
10		156.74	157.32	Sample is 75% pure qtz & carb (vn) & 30% carbonitized GND selvage, all quite crumbly.	0	1	0	1	4	
10		157.32	158.82	One huge (150cm) qtz/carb vn. 5% sulphides (half oxidized) disseminated throughout. Quite soft (5) & crumbly, opaque white.	0	0	0	0	4	
10		158.82	166.82	Mod'ly alt'd GND. Broken up to ~10cm chunks avg. Grey qtz vns w/ irregular edges & no real orientation. From 162-162.5m: low angle grey qtz vn appears folded. Lack of selvage also suggests post-vn mmphsm/ 2nd intrusion/ degree of heat to reset GND as unalt'd. Selvages relation to vn size is cryptic. Next small vn has large selvage (diff comp - may be part of later vein episode).	0	2	1	0	2	
10		166.82	169.99	Section dominated by large qtz/carb vns (1.03m & 1.46m wide). 3.17m total, 2.49m vn at 168.35m, (40cm section btwn >1m vns), one small selvage has ox'd py smeared onto frac face; treated as vn even though it has obviously been sheared.	0	1	1	0	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							s	2																					
4	1	2.0	4.5	50		6.0	q	3			15.0		1.0					1.0	3.0			B292162	149.35	150.88	**0.046**	DUP		VA050549843	1.53
							chl	3																					
							s	2																					
4	1	1.0	4.0	50		8.0	q	3			5.0							1.0				B292163	150.88	151.69	**0.172**			VA050549843	0.81
							chl	3																					
							s	2																					
5	1	1.0	4.0	45		3.0	q	3	0		5.0											B292164	151.69	152.40	**0.099**			VA050549843	0.71
							chl	1																					
							s	4																					
							cb	1																					
6	1	1.0	4.0	45		2.0	q	3	0		7.0											B292165	152.40	153.92	**0.009**			VA050549843	1.52
							chl	1																					
							s	4																					
							cb	1																					
3	1	1.0	2.0	45		10.0	q	2	0		1.0											B292166	153.92	154.58	**0.012**			VA050549843	0.66
							chl	3																					
							s	2																					
							cb	1																					
5	1	1.0	4.5	60	20		q	1	0	10.0								4.0				B292167	154.58	155.62	**0.257**			VA050549843	1.04
							chl	4																					
							s	4																					
							cb	2																					
2	1	2.0	4.0	50			q	1	0	4.0								4.0				B292168	155.62	156.74	**0.063**			VA050549843	1.12
							chl/s	4																					
							cb	2																					
2	1	2.0	4.0	50			q	1	0	4.0								4.0				B292169	155.62	156.74	**0.059**	PD/CA		VA050549843	1.12
							chl/s	4																					
							cb	2																					
																						B292170	STANDARD 7G		**4.36**	7G		VA050549843	
2	3	20.0	22.0	30			q	3	1	3.0			2.0					2.0	0.0			B292171	156.74	157.32	**0.055**			VA050549843	0.58
							cb	4																					
							s	2																					
1	3	150.0	150.0	50		0.0				3.0			2.0					4.0	2.0			B292172	157.32	158.82	**0.042**		Selvage not incl. in sample (only vn).	VA050549843	1.50
0																						B292173	158.82	160.02	**0.013**			VA050549843	1.20
2	1	1.5	2.5	30	65	3.0	q	3		3.0			1.0					4.0				B292174	160.02	161.54	**0.016**			VA050549843	1.52
							chl	3																					
3	1	4.0	9.0	10		1.0	q	2		0.0												B292175	161.54	163.07	**0.012**			VA05051469	1.53
							chl	4																					
																						B292176	BLANK		**<0.005**			VA05051469	
1	1	1.0	1.0	25		2.0	q	3					10.0						3.0			B292177	163.07	164.59	**0.016**			VA05051469	1.52
							chl	2																					
3	1	1.0	3.0	30		20.0	q	3			12.0	1.0	0.1					0.0	0.0			B292178	164.59	166.82	**0.049**			VA05051469	2.23
							chl	3																					
							s	2																					
							cb	2																					
1	3	6.0	6.0	10		3.0	q	3	0	3.0			2.0						2.0										
							cb	1																					
							s	1																					
							chl	2																					
1	3	103.0	103.0	30		16.0	q	2	0	8.0	1.0		2.0					4.0	1.0			B292179	166.82	168.18	**0.08**		Selvages included	VA05051469	1.36
							chl	4																					
							s	2																					
							cb	2																					
1	3	1.0	1.0	50		8.0	q	2	0	10.0								4.0				B292180	168.18	168.71	**0.014**			VA05051469	0.53
							chl	4																					
							s	2																					
							cb	2																					
1	3	128.0	128.0	60		0.0				5.0	1.0		1.0					4.0	3.0			B292181	168.71	169.99	**0.017**		Selvage not incl.	VA05051469	1.28
1	3	128.0	128.0	60		0.0				5.0	1.0		1.0					4.0	3.0			B292182	168.71	169.99	**0.01**	DUP		VA05051469	1.28

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		169.99	183.82	Minor carb alt'n around qtz/carb vns & through vnlets. Otherwise v. minorly alt'd GND.	0	1	1	0	2	
10		183.82	184.80	Beginning gradation to heavily chloritized GND. Half of sample is v. alt'd w/ ser & chl. Unalt'd GND appears v. mafic (qtz <20%) w/ milky qtz vns.	0	3	3	0	1	
10		184.80	185.93	70% alt'd GND here. Appears in bands, selvage around qtz/carb vns.	0	2	4	0	2	
10		185.93	187.45	Crumbly, carb-rich, highly chloritized rock. No evidence of shear.	0	2	4	2	3	
10		187.45	205.26	GND chl'd. Color medium teal green to deep greenish grey. Reg fracs at 60-70° to CA. Smooth appearance, aphanitic. Med-sized qtz vns (~2-3/m) run through entire section. Vnlets of calcite are also frequent (~20/m), at 60° & 0° to CA. Qtz vns have a varying amount of calcite w/in them, from 0-90% - noted per sample on 2nd page: if calcite <50%, it is considered a "1", if >50%, "3"-type vein. @ 202.00-202.69m: a banded section w/ ox'd py in chunks to vnlets surrounds broken & rounded qtz vns.	0	2	5	0	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
1	1	3.0	3.0	55		0.5	q	5	0	0.0												B292183	169.99	170.69	**0.005**			VA05051469	0.70
8	1	2.0	5.5	30	55	2.0	q	3		2.0	8.0	1.0						4.0				B292184	170.69	172.21	**1.996**			VA05051469	1.52
							chl	3																					
							s	1																					
							cb	1																					
1	3	1.0	1.0	45		6.0	q	2			3.0		10.0						3.0			B292185	172.21	173.74	**0.014**			VA05051469	1.53
							chl	3																					
							s	1																					
							cb	3																					
7	1	1.0	3.0	50	10	2.0	q	3	0	3.0	8.0		10.0					3.0	2.0			B292186	173.74	175.26	**0.046**			VA05051469	1.52
							s	2																					
5	1	1.0	2.0	50	20	1.0	q	3	0	5.0			10.0					0.0	3.0			B292187	175.26	176.78	**0.019**			VA05051469	1.52
							s	2																					
5	1	3.0	5.0	50		1.0	q	3	0	3.0			5.0					0.0	3.0			B292188	176.78	178.31	**0.022**			VA05051469	1.53
							s	2																					
5	1	3.0	5.0	50		1.0	q	3	0	3.0			5.0					0.0	3.0			B292189	176.78	178.31	**0.017**	PD/CA		VA05051469	1.53
							s	2																					
																						B292190	STANDARD 1A		**0.861**	1A		VA05051469	
3	1	4.0	8.5	40	50	8.0	q	3			10.0		5.0						1.0			B292191	178.31	179.83	**0.009**			VA05051469	1.52
							s	2																					
6	1	2.0	7.0	60	30	5.0	q	3			2.0		2.0						3.0			B292192	179.83	181.36	**0.008**			VA05051469	1.53
							s	2																					
							chl	3																					
5	1	1.0	5.0	45		4.0	q	3			6.0		4.0					0.0	0.0			B292193	181.36	182.88	**0.052**			VA05051469	1.52
							s	2																					
							chl	2																					
3	1	1.5	3.0	40		2.0	q	3					5.0						3.0			B292194	182.88	183.82	**0.024**			VA05051469	0.94
							s	3																					
							chl	2																					
4	1	1.0	2.5	30		2.0	q	3	0		3.0		1.0						3.0			B292195	183.82	184.80	**0.083**			VA05051469	0.98
							chl	2																					
							s	3																					
																						B292196	BLANK		**<0.005**			VA05051469	
6	3	0.5	2.5	40	50	8.0	q	1		5.0								5.0				B292197	184.80	185.93	**0.111**			VA05051469	1.13
							chl	4																					
							s	3																					
							cb	2																					
4	1	5.0	16.0	60	30		chl	4					3.0						3.0			B292198	185.93	187.45	**0.123**			VA05051469	1.52
							s	2																					
							cb	2																					
3	1	5.5	13.0	55			chl	4		8.0	2.0		1.0					3.0	1.0			B292199	187.45	188.98	**0.643**			VA05051469	1.53
							s	2																					
							cb	2																					
2	3	1.0	1.5	55																									
4	1	0.5	2.0	50			chl	4		3.0			1.0					4.0	3.0			B292200	188.98	190.50	**1.115**			VA05051469	1.52
							s	2																					
							cb	2																					
1	3	0.5	0.5	50			chl	4		1.0								5.0											
							s	2																					
							cb	2																					
3	1	3.5	9.5	50			chl	4					4.0						2.0			B292201	190.50	192.02	**0.43**			VA05051469	1.52
							s	2																					
							cb	2																					
3	1	3.5	9.5	50			chl	4					4.0						2.0			B292202	190.50	192.02	**0.248**	DUP		VA05051469	1.52
							s	2																					
							cb	2																					
3	1	3.0	6.0	50			chl	4		3.0			1.0					4.0	4.0			B292203	192.02	193.55	**0.061**			VA05051469	1.53
							s	2																					
							cb	2																					
2	3	0.5	1.0	50						0.0																			
4	1	2.0	4.5	50			chl	4		5.0			2.0					1.0	1.0			B292204	193.55	195.07	**0.127**			VA05051469	1.52
							s	2																					

DRILL LOG LEGEND P1	DATE: June 11-16th, 2005 PAGE 13 of 14		
DRILL HOLE # : DG05-283C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		202.69	204.22	Interesting vns; all are 1cm width, one qtz vn is folded & sheared (brittle ductile, see picture). Carb vns are overprinted & moved by qtz vns in some places. Look partially syn-intrusive because of appearance of both w/in small areas & mixing btwn the 2 in most vns.						
				Last 18cm of section 205.08-205.26m is grading out of chloritic section. Appears as selvage, more granular texture, more GND-ish.						
10		205.26	205.74	Still somewhat chl'd but GND texture visible again & color is deep greenish grey.	0	2	2	0	0	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 11 to 16, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																			
						Selvages				Sulphides								Oxidation					Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							cb	2																					
1	3	3.0	3.0	50			chl	4		3.0								2.0											
							s	2																					
							cb	2																					
4	1	4.0	12.0	50			chl	4		13.0	3.0							2.0				B292205	195.07	196.60	**0.193**			VA05051469	1.53
							s	2																					
							cb	2																					
5	1	2.0	4.0	55			chl	4		7.0			1.0					4.0				B292206	196.60	198.12	**0.138**			VA05051469	1.52
							s	2																					
							cb	2																					
5	1	4.0	11.0	55						6.0	4.0							4.0				B292207	198.12	199.64	**0.566**			VA05051469	1.52
5	1	5.0	9.0	55						3.0	1.0							4.0				B292208	199.64	201.17	**2.82**			VA05051469	1.53
5	1	5.0	9.0	55						3.0	1.0							4.0				B292209	199.64	201.17	**3**	PD/CA		VA05051469	1.53
																						B292210	STANDARD 4D		**1.56**	4D		VA05051469	
4	1	2.0	8.0	55						20.0								5.0				B292211	201.17	202.69	**0.381**			VA05051469	1.52
3	6	1.0	2.0	55		0.0				95.0	5.0							5.0											
6	1	1.0	6.0	50	60		chl	4		2.0								1.0				B292212	202.69	204.22	**0.323**			VA05051469	1.53
							s	2																					
							cb	2																					
3	3	1.0	3.0	50			chl	4		1.0								5.0											
							s	2																					
							cb	2																					
8	1	2.5	7.5	65	50		chl	4		5.0								3.0				B292213	204.22	205.26	**0.324**			VA05051469	1.04
							s	2																					
							cb	2																					
1	1	1.0	1.0	60		6.0	q	1	0	3.0	1.0							5.0				B292214	205.26	205.76	**0.363**			VA05051469	0.50
							chl	3																					
							s	3																					
							cb	1																					
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-284C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:	865m
BEARING: 000	DIP: -50°
COORD SYSTEM: NAD 27:	EASTING: 459105 NORTHING: 7099382
COORD SYSTEM: NAD 83:	EASTING: 458987 NORTHING: 7099570
NAD 27 (CORRECTED for historic grid):	EASTING: 459075 NORTHING: 7099392
SECTION LINE 459075 (historic grid)	

DATE STARTED: 15-Jun-05 DATE COMPLETED: 17-Jun-05

LOGGED BY: Terry Croteau & Kristian Whitehead

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 10.67m
Deviation:
Casing: 10.67m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B292980-B293000 and B380201-B380246
Requisition #: MASP448STRGOL.05Q — Date Shipped: 21-June-05
Lab Record #: VA05052040 — Date Received: 30-June-05

Sample Sequence: B380247-B380300
Requisition #: MASP448STRGOL.05Q — Date Shipped: 24-June-05
Lab Record #: VA05054218 & VA05053956(301-306) — Date Received: 05-July-05

Sample Sequence: B290356-B290387 (returns)
Requisition #: MASP448STRGOL.05Q — Date Shipped: 24-June-05
Lab Record #: VA05053955 — Date Received: 04-July-05

Duplicates:	B292982, B380202; B380222; B380242; B380262; B380282; B380302
Preparation Duplicate/ Check Assay:	B292989; 380209; 380229; 380249; 380269; 380289
Standards:	B292990 (3C); B380210 (4D); B380230(1A); B380250 (6F); B380270 (6F); 380290 (3C)
Blanks:	B292996; B380216; B380236; B380256; B380276; B380296

FROM	TO	LITHOLOGY
10.67	107.40	MSED - ARGL w/ QZZ layers
107.40	114.83	GND
114.83	134.71	MSED - ARGL w/ QZZ layers
134.71	135.72	GND
135.72	138.68	MSED - ARGL w/ QZZ layers

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
50	341	-51.7	007	008
67.06	341.5	-52	007.5	008.5
100	342	-53.9	008	009
138.68	342.1	-54.7	008.1	009.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 1 of 6	
DRILL HOLE # : DG05-284C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-10.67	0.00	10.67	Casing (No core recovered)						
80	10.67-18.29	10.67	18.29	MSED: Meta sediments (argillite) , foliations are mm scale w/ foliations at 10-11 metres at 60 ° wi limonite semi pervasive on foliation; lim predominant on fractures. Core is black with minor qtz boudins and stringers, no sulphides present at surface. Not silicified (scratches with nail).	3					
12	18.29-19.30	18.29	19.30	GNDD (Granodiorite Dike), upper contact not vis. Broken core, qtz vn wi dissem aspy (tr) pieces; lower ctc at 60-65°		2		3		
80	19.3-21.54	19.30	21.54	Meta-Sediments; very broken core; Foliation at 40-50°; GND vein at 40° (7cm); qtz veins at 90° to GND dike at 20° (or 155°) TCA; trace diss aspy; GND intruded metaseds parallel to foliation at 40° TCA						
10	21.54-22.49	21.54	22.49	GND; broken core; sections of bleached GND with sulphides and quartz veinlets		2		3		
80	22.49-67.91	22.49	57.91	MSED; Foliation at 0° or parallel to CA; upper contact at 40° TCA						
				At 24.47m MSED's become silicified and core badly broken						
				At 27.43m recovery increases; Foliations and crenulations at 45° TCA to as steep as 85° TCA at 30.78m						
80		35.05	36.58	MSED foliation at 45° TCA; hematite on fracture surfaces; veinlets running at 45° TCA contain trace cpy in vein; At 35.56 3 cm GND dyke at 40° TCA; broken qtz vn present with weathered aspy						
80		36.58	38.10	MSED; Foliation to 0 ° TCA and becomes crenulated; changes to 30 ° TCA at 37.62m; Sheeted vn set at 37.06m at 40 ° TCA (3 0.5 cm qtz vns)						
80		38.10	39.62	MSED; Good recovery; lim on fracture surfaces; Foliation at 70° to 45° TCA at 38.3m						
80		39.62	42.34	MSED; Foliation at 50 ° TCA; Core becomes darker (more arg?) and broken; Recovery decreases, becoming very poor (30% at 41.15m)						
				At 40.20m - 3 cm and 4 cm qtz veins; grey qtz at 60° TCA; trace aspy; gravel sized MSED at 42.04m						
80		42.34	43.30	Core becomes bleached (silicified) and contains 10 - 15% subhedral aspy and 5% py; at 42.95m core becomes gougy; small qtz pieces and argillite present in gouge; gouge to 7cm at 45° TCA						5
80		43.30	44.50	Poor core recovery; core is commonly reduced to gravel size or smaller pieces (<1.5cm); broken qtz vns are present in gravel; solid pieces of core show lineations @85° TCA						
80		44.50	50.29	Foliation at 85° TCA; trending to 50° at 46.84m; Heavy limoninte staining in fractures; Core recovery is good; At 49.59m, 18cm bleached, silicified section related to 3cm qtz vein.						
		50.29	51.82	Core is silicified and intruded by bleached GND dykes (3cm) dykes cut through 1cm qtz vein; hem staining absent; MSED becomes fragmented into gravel size pieces; core recovery becomes very poor						
		51.82	54.86	Core recovery poor; numerous vnlts throughout; Foliation continues at 45-50 °; often crenulated						
		54.86	56.39	Core is dark green, chloritized (?); Euhedral aspy crystals disseminated throughout; Gouge at 54.16m (5cm); qtz eyes; core becomes black (argillite) with foliation at 50° TCA			4			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						Casing	0.00	10.67					
																						B292980	10.67	12.19	0.006			VA05052040	1.52
										1.0												B292981	12.19	13.72	0.019		V. minor qtz pieces; Py on frac surface	VA05052040	1.53
										1.0												B292982	12.19	13.72	0.011	DUP		VA05052040	1.53
																						B292983	13.72	15.24	0.017		Very poor core recovery	VA05052040	1.52
1	1	35.0	35.0										0.1									B292984	15.24	16.76	0.015			VA05052040	1.52
																						B292985	16.76	18.29	0.051		Very poor core recovery	VA05052040	1.53
1	1												0.1									B292986	18.29	19.81	0.041			VA05052040	1.52
3	1	0.75	1.0	40	20								0.1									B292987	19.81	21.34	0.023			VA05052040	1.53
	2	0.5	1.0	20		20.0		2	1	0.1			0.1					4.0				B292988	21.34	22.26	0.011			VA05052040	0.92
	2	0.5	1.0	20		20.0		2	1	0.1			0.1					4.0				B292989	21.34	22.26	0.011	PD/CA		VA05052040	0.92
																						B292990	STANDARD 3C		0.098	3C		VA05052040	
																						B292991	22.26	22.49	0.006		Nothing Significant	VA05052040	0.23
1	1	0.25	0.25	20		0.0																B292992	22.49	23.95	0.010			VA05052040	1.46
3	1	5.0	5.5	30	35								0.1									B292993	23.95	24.47	0.006			VA05052040	0.52
																						B292994	24.47	25.91	0.008		1, 3.5 cm quartz piece	VA05052040	1.44
																						B292995	25.91	27.43	0.007		Quartz pieces, no visible sulphides	VA05052040	1.52
																						B292996	BLANK		<0.005			VA05052040	
3	1	0.5	1.0	20	30																	B292997	27.43	28.96	<0.005			VA05052040	1.53
2	1	0.5	1.0	30																		B292998	28.96	30.48	<0.005			VA05052040	1.52
2	1	0.25	0.5	60																		B292999	30.48	32.00	<0.005			VA05052040	1.52
																						B293000	32.00	33.53	0.008			VA05052040	1.53
																						B380201	33.53	34.42	0.006			VA05052040	0.89
																						B380202	33.53	34.42	0.006	DUP		VA05052040	0.89
																						B380203	34.42	35.05	0.013			VA05052040	0.63
4	1	1.0	2.5	45		0.0							0.1									B380204	35.05	36.58	0.007			VA05052040	1.53
8	1	1.0	2.5	40		0.0							10.0						3.0			B380205	36.58	38.10	0.018			VA05052040	1.52
3	1	0.2	0.6	40	10	0.2	q	3	1				5.0									B380206	38.10	39.62	0.010			VA05052040	1.52
2	1	4.0	7.0	60		0.0							0.1									B380207	39.62	40.47	0.011			VA05052040	0.85
2	1	0.5	0.7	40									1.0									B380208	40.47	41.15	0.007			VA05052040	0.68
2	1	0.5	0.7	40									1.0									B380209	40.47	41.14	0.007	PD/CA		VA05052040	0.67
																						B380210	STANDARD 4D		0.469	4D		VA05052040	
																						B380211	41.15	42.34	0.038			VA05052040	1.19
																						B380212	42.34	43.30	0.196			VA05052040	0.96
2	1	0.3	0.6	30									10.0									B380213	43.30	44.50	0.017			VA05052040	1.20
																						B380214	44.50	45.72	0.009			VA05052040	1.22
2	1	2.0	5.0	70		0.0							2.0									B380215	45.72	47.24	0.010			VA05052040	1.52
																						B380216	BLANK		<0.005			VA05052040	
2	1	0.3	0.5	35		0.2	q	2	0				10.0						60.0			B380217	47.24	48.79	0.006			VA05052040	1.55
5	1	2.0	2.8	20		0.0							3.0						10.0			B380218	48.79	49.59	0.013			VA05052040	0.80
3	1	3.0	8.0	30		5.0	q	5	0	5.0			10.0						70.0			B380219	49.59	50.29	0.021			VA05052040	0.70
5	1	2.0	7.0	30		4.0	q	5	0	10.0			15.0					90.0	10.0			B380220	50.29	51.82	0.014			VA05052040	1.53
4	1	1.0	1.8	30		0.0							10.0						30.0			B380221	51.82	53.34	0.021			VA05052040	1.52
4	1	1.0	1.8	30		0.0							10.0						30.0			B380222	51.82	53.34	0.008	DUP		VA05052040	1.52
3	1	3.0	5.0	40		2.0	q	5	0	20.0			5.0					1.0				B380223	53.34	54.86	0.008			VA05052040	1.52
4	1	3.0	3.6	70		0.0				10.0			10.0									B380224	54.86	56.39	0.037			VA05052040	1.53

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 3 of 6	
DRILL HOLE # : DG05-284C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
		56.39	57.91	Core becomes clay rich and altered; Recover is very poor (32%); QZZ starts to appear as frags at 57.60m; contact btw QZZ and MSEDs not visible						
70	57.91-67.45	57.91	67.45	Quartzite (QZZ) - Fine grained; Pyrite on some fractures; disseminated and aspy also present diss throughout: veinlets carry abndt aspy; Recovery good (75%)						
80	67.45-72.10	67.45	71.33	MSED with foliation angles at 60° TCA; diss py and aspy present throughout; At 67.98m 5 cm gouge at 60°; At 70.77m 4cm gg at 70° TCA; foliation is crenulated 69.65 to 69.85m						
		71.33	72.10	Metaseds more silicified; Quartzite? Clayey gouge at 71.43m, 6cm, at 60° TCA; At 71.81m a 5cm grey quartz vein, fractured, at 80° TCA.						
70	72.10-76.20	72.10	73.15	QZZ/MSED ctc; interbedded through interval; At 73.05m 10cm grey qtz vein at 45° TCA						
70		73.15	76.20	QZZ; Good rec, diss aspy throughout; sulphide veinlets at 75.36 to 75.45m						
80	76.20-76.90	76.20	76.90	MSED; Foliation at 60°; high silicic alteration; At 76.25m a 7cm qtz vein; vugs present, possibly due to weathering out of sulphides						
70	76.90-78.42	76.90	78.42	QZZ; Sulphide veinlets (py) present; 11cm vein at 77.92m; vugs with weathered aspy present						
80	78.42-85.34	78.42	82.30	MSED; Foliation at 65-70° TCA throughout; MSEDS are altered heavily around selvages via silica or chlorite; at 81.95m 9cm clayey gouge qtz and MSED frags.						
		82.30	85.34	MSEDS black with foliation at 50° TCA; at 82.51m to 82.76m altered to clay; very micaceous; Diss aspy and po present; Euhedral aspy crystals present on some fractures						
70	85.34-107.40	85.34	90.62	QZZ; Transitions from MSED to QZZ' initial foliations at 60° reducing after 86.05m to absent by 88.39m; Initially core is broken, becoming more competent as QZZ more dominant at 88.05m						
70		90.62	92.96	QZZ with interbedded MSED; MSED black and micaceous (biot) to argillic; no visible foliation in MSEDS at 50° TCA; Core is broken; At 92.08m 6cm clayey gouge at 50° TCA; Diss py in gouge; Qtz eyes						
70		92.96	96.75	QZZ; Good core rec; diss py present; vugs filled wi py						
70		96.75	103.13	QZZ with interbedded MSED; Recovery decreases; Foliations at 45° where vis; often crenulated; Qtz stringers running at 30° TCA contain aspy.						
70		103.13	107.40	QZZ; Carbonate present on most fractures; occasionally found wi py on top of slickenslides; numerous vnlts fill wi py or oxidized py; at 107.4m GND ctc at 45° TCA						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration, 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B380225	56.39	57.91	0.158			VA05052040	1.52
0																						B380226	57.91	59.94	0.006			VA05052040	2.03
0																						B380227	59.94	60.96	0.006			VA05052040	1.02
10	1	0.1	1.0	40		0.0							10.0									B380228	60.96	62.48	0.033			VA05052040	1.52
10	1	0.1	1.0	40		0.0							10.0									B380229	60.96	62.48	0.038	PD/CA		VA05052040	1.52
																						B380230	STANDARD 1A		0.870	1A		VA05052040	
2	1	4.0	8.0	40		0.0							10.0									B380231	62.48	64.01	0.017			VA05052040	1.53
																						B380232	64.01	65.53	0.024			VA05052040	1.52
7	6	0.1	0.7	30		0.0							90.0									B380233	65.53	67.06	0.062			VA05052040	1.53
0																						B380234	67.06	67.45	0.012			VA05052040	0.39
																						B380235	67.45	68.58	0.022			VA05052040	1.13
																						B380236	BLANK		<0.005			VA05052040	
3	1	0.4	1.0	45		0.0				5.0			10.0									B380237	68.58	70.10	0.014			VA05052040	1.52
1	1	1.0	1.0	87		0.0				10.0			5.0									B380238	70.10	71.33	0.060			VA05052040	1.23
3	1	6.0	8.0	80	10	9.0	q/chl	4	1	10.0								10.0				B380239	71.33	72.10	0.044			VA05052040	0.77
4	1	10.0	19.0	60	45	10.0	q/chl	4	1				10.0									B380240	72.10	72.65	<0.005			VA05052040	0.55
4	1	10.0	17.0	45		10.0	q/chl	4	1				10.0									B380241	72.65	73.15	0.007			VA05052040	0.50
4	1	10.0	17.0	45		10.0	q/chl	4	1				10.0									B380242	72.65	73.15	0.008	DUP		VA05052040	0.50
7	1	3.5	15.0	45		5.0	q	5	1				5.0									B380243	73.15	74.68	<0.005			VA05052040	1.53
4	1	4.0	12.0	65		5.0	q	5	1				5.0									B380244	74.68	75.36	0.008			VA05052040	0.68
3	6	0.1	0.4	45		0.0				100.0												B380245	75.36	75.76	<0.005			VA05052040	0.40
6	1	2.0	3.2	45	80	4.0	q	5	1				10.0									B380246	75.76	76.90	0.074			VA05052040	1.14
1	6	0.2	0.2	55						100.0												B380247	76.90	78.42	<0.005			VA05054218	1.52
6	1	11.0	19.0	60		6.0	q	5	1														(77.92	78.03)					
8	1	4.0	8.5	60		8.0	q	5	1	20.0			5.0									B380248	78.42	79.25	0.008			VA05054218	0.83
8	1	4.0	8.5	60		8.0	q	5	1	20.0			5.0									B380249	78.42	79.25	0.013	PD/CA		VA05054218	0.83
																						B380250	STANDARD 6F		2.860	6F		VA05054218	
1	1	1.0	1.0	60		0.0							5.0									B380251	79.25	80.77	0.011			VA05054218	1.52
2	1	0.5	1.0	60		0.0																B380252	80.77	82.30	0.016			VA05054218	1.53
2	4	0.2	0.4	50																		B380253	82.30	83.82	0.027			VA05054218	1.52
3	1	1.0	1.5	50						10.0	3.0		3.0				1.0						(82.51	82.76)					
3	6	0.2	0.6	30	10								5.0					70.0				B380254	83.82	85.34	0.017			VA05054218	1.52
2	1	0.2	0.4	40		0.0				10.0			10.0									B380255	85.34	86.87	0.104			VA05054218	1.53
																						B380256	BLANK		<0.005			VA05054218	
3	6	0.2	0.6	20		0.0				100.0								70.0				B380257	86.87	88.39	0.014			VA05054218	1.52
1	6	0.2	0.2	40						10.0			80.0					15.0				B380258	88.39	89.92	0.052			VA05054218	1.53
2	1	0.2	0.4	45		0.0							0.1									B380259	89.92	91.44	0.007			VA05054218	1.52
2	6	0.2	0.4	35		0.0							70.0									B380260	91.44	92.96	<0.005			VA05054218	1.52
0																						B380261	92.96	94.49	0.007			VA05054218	1.53
																						B380262	92.96	94.49	0.018	DUP		VA05054218	1.53
3	6	0.2	0.6			0.0				90.0			10.0					70.0				B380263	94.49	96.01	0.071			VA05054218	1.52
0																						B380264	96.01	97.54	0.153			VA05054218	1.53
0																						B380265	97.54	99.06	0.153			VA05054218	1.52
4	6	0.2	1.0	45		0.0				20.0			60.0					25.0				B380266	99.06	100.58	0.106			VA05054218	1.52
4	1	0.1	1.6	60	45	0.0				10.0			10.0		10.0			90.0				B380267	100.58	102.11	0.058			VA05054218	1.53
1	4	0.2	0.2	35		0.0																B380268	102.11	103.63	0.025			VA05054218	1.52
1	4	0.2	0.2	35		0.0																B380269	102.11	103.63	0.028	PD/CA		VA05054218	1.52
																						B380270	STANDARD 6F		2.850	6F		VA05054218	
0																						B380271	103.63	105.06	0.037			VA05054218	1.43
1	1	5.0	5.0	20		0.0							1.0									B380272	105.06	106.68	<0.005			VA05054218	1.62
0																						B380273	106.68	107.40	0.062			VA05054218	0.72
2	6	3.0	5.0	55		0.0				30.0			60.0					60.0	40.0			B380274	107.40	108.26	0.517			VA05054218	0.86

DRILL LOG LEGEND P1	DATE: June 18 to 21st, 2005	PAGE 5 of 6		
DRILL HOLE # : DG05-284C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	107.40-114.83	107.40	109.34	Appears to be extremely weathered GND; Difficult to tell due to intense alteration; Core is badly decomposed with very poor recovery; sugary texture; 40% qtz 20% plag 5% Hbl; Bt appears to be absent due to alteration; Alt'd to ser and chl; Qtz veins are broken, remnant massive sulphide vein at 107.96m, 2cm at 55° TCA; Diss py present throughout.		4	3	2		
10		109.34	110.65	GND more competent; Alteration less intense; Disseminated aspy present; Veins contain more sulphides in areas of chloritic alteration		2	2	1		
10		110.65	114.83	QZZ with GND Dyke (?); At 110.65m, 7cm at 80° TCA; Sulphide veins in Dyke, altered by QZZ contains 30% aspy; At 110.80m, 12cm at 80° TCA						
				Euhedral aspy on fracture at 114.26m mnr py also present; 10cm qtz vein at 114.58m; Diss aspy present throughout						
80	114.83-117.17	114.83	117.17	MSED; Black with foliations at 50° TCA; Lineations are crenulated; veins have large selvages; Fractures parallel TCA filled with carb						
70	117.17-123.58	117.17	123.58	QZZ wi interbedded MSED; Foliations at 50°; QZZ host to sulphide veinlets; py and aspy						
80	123.58-134.11	123.58	134.11	MSED; Foliations predom at 45° TCA but locally at 85° at 126.90 to 126.96m and at 128.02 to 128.13m; Boudins and crenulation present						
80	134.11-134.71	134.11	134.71	MSED; Silicified metased and quartzite; no vis ctc; At 134.56m contact with bleached intrusive						
10	134.71-135.72	134.71	135.72	GND med grained bleached intrusive; Alteration makes it difficult to identify less altered section 40% qtz, 20% plag and 15% biot; Likely GND						
80	135.72-138.68	135.72	137.56	MSED; Foliation at 40°; local banding altered to chlorite at 136.82m						
80		137.56	138.68	MSED wi small GND dykes; 8cm at 137.56m at 50° TCA; 4cm at 137.86m at 50° TCA; gouge at 137.96m 20cm at 50° TCA						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 18 to 21st, 2005

LOGGED BY: K. Whitehead & T Croteau

PAGE 6 of 6

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation						From	To					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
3	1	0.2	0.6																			B380275	108.26	109.34	0.714		Unable to determine orientation due to decomp.	VA05054218	1.08
																						B380276	BLANK		0.005			VA05054218	
1	4	0.2	0.2	45																		B380277	109.34	110.65	0.250			VA05054218	1.31
2	1	0.4	0.6	50		2.0	q/chl	4	0													B380278	110.65	111.08	0.573			VA05054218	0.43
0																						B380279	111.08	111.98	0.085			VA05054218	0.90
4	1	0.4	0.9	25		0.0				15.0			25.0						60.0			B380280	111.98	113.38	0.056			VA05054218	1.40
1	6	0.2	0.2	30		0.0							100.0									B380281	113.38	114.30	0.053			VA05054218	0.92
1	6	0.2	0.2	30		0.0							100.0									B380282	113.38	114.30	0.090	DUP		VA05054218	0.92
1	1	10.0	10.0	65		0.0							1.0									B380283	114.30	114.83	0.005			VA05054218	0.53
1	1	0.2	0.2	70						0.1			0.1									B380284	114.83	115.82	0.050			VA05054218	0.99
3	1	1.0	0.17	60		0.0							5.0									B380285	115.82	116.97	0.005			VA05054218	1.15
3	1	3.0	4.0	60	35	0.0							20.0						80.0			B380286	116.97	118.36	0.150			VA05054218	1.39
2	1	1.0	1.4	40		0.0				15.0			20.0									B380287	118.36	119.88	0.029			VA05054218	1.52
0																						B380288	119.88	121.39	0.045			VA05054218	1.51
																						B380289	119.88	121.39	0.038	PD/CA		VA05054218	1.51
																						B380290	STANDARD 3C		0.088	3C		VA05054218	
0																						B380291	121.39	122.91	0.039			VA05054218	1.52
0																						B380292	122.91	123.64	0.006			VA05054218	0.73
4	1	1.0	2.4	60		0.0				0.1			0.1									B380293	123.64	124.42	0.016			VA05054218	0.78
1	1	1.0	1.0	60		0.0							1.0						90.0			B380294	124.42	125.94	0.043			VA05054218	1.52
1	1	3.0	3.0	60		0.0							0.1									B380295	125.94	126.49	0.064			VA05054218	0.55
																						B380296	BLANK		<0.005			VA05054218	
1	1	1.0	1.0	30		0.0				5.0			10.0					40.0	10.0			B380297	126.49	128.02	0.026			VA05054218	1.53
2	1	2.0	3.0	45		2.0	q/chl	3	1	5.0												B380298	128.02	129.54	0.017			VA05054218	1.52
2	6	1.0	1.2	45		0.0							10.0									B380299	129.54	131.06	0.017			VA05054218	1.52
1	1	1.0	1.0	45		0.0																B380300	131.06	132.59	0.005			VA05054218	1.53
1	4	1.0	1.0	45																		B380301	132.59	134.11	0.006			VA05053956	1.52
1	4	1.0	1.0	45																		B380302	132.59	134.11	0.011	DUP		VA05053956	1.52
2	6	0.2	0.4	45		0.0				25.0												B380303	134.11	134.71	0.032			VA05053956	0.60
2	6	0.2	0.4	45		0.0				10.0								80.0				B380304	134.71	135.68	0.113			VA05053956	0.97
1	1	2.0	2.0	40		0.0																B380305	135.68	137.56	0.010			VA05053956	1.88
1	1	2.0	2.0	60		5.0	chl	4	1				10.0									B380306	137.56	138.68	0.009			VA05053956	1.12
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-285C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:	1028m
BEARING: 000	DIP: -50°
COORD SYSTEM: NAD 27:	EASTING: 459753 NORTHING: 7099042
COORD SYSTEM: NAD 83:	EASTING: 459633 NORTHING: 7099227
NAD 27 (CORRECTED for historic grid):	EASTING: 459723 NORTHING: 7099052
SECTION LINE 459725 (historic grid)	

DATE STARTED: 16-Jun-05 DATE COMPLETED: 19-Jun-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ
Overburden: 14.02m
Deviation:
Casing: 14.02m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A

Notes: No plug necessary. Drill oriented by K. Whitehead. EOH corrected by DH (Nov).

FROM	TO	LITHOLOGY
14.02	36.58	MSED
36.58	192.02	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B292215 - B292378
Requisition #: MASP448STRGOL.05Q Date Shipped: 21-Jun-05
Lab Record #: VA05052412 Date Received: 29-Jun-05

Duplicates:	292222; 292242; 292262; 292282; 292302; 292322; 292342; 292362
Preparation Duplicate/ Check Assay:	292229; 292249; 292269; 292289; 292309; 292329; 292349; 292369
Standards:	292230 (5E); 292250 (2B); 292270 (6F); 292290 (7G); 292310 (6F); 292330 (1A); 292350 (5E); 292370 (4D)
Blanks:	292216; 292236; 292256; 292276; 292296; 292316; 292336; 292356; 292376

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+ 27 Corr)
75	337.9	-51	3.9	4.9
150	336.6	-52.6	2.6	3.6
192.02	338.8	-52.8	4.8	5.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1

DRILL HOLE # : DG05-285C

DATE: 16-19-Jun-05 PAGE 1 of 12

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From:	To:	Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-14.02	0.00	14.02	Casing (No Recovery)						
80	14.02-36.58	14.02	18.29	MSED; Appearance is black with finely laminated layering (meta-beds), distinguished by minor compositional variation; Complex structure, bedding is from 0 to 60° to CA; qtz veins are parallel to bedding AND convoluted in shape and girth; Cross cutting bedding; very minor limonite.	1				1	
80		18.29	21.34	Veins <1cm through MSED; variable orientations throughout; weakens rock. Gouge section abuts competent (but crumbly) rock at 30° to CA; Gouge length is 20 cm. Bigger veins from 19.81m to 20.34m appear rearranged (see diag in written log); ox'd py concentrated in lenses at margins.	2			1	2	
80		21.34	22.86	Gouge - brecciated MSED, limonite more pervasive where core is broken	2		1	2	2	
80		22.86	24.38	Veins <1cm following bedding plane (30° to CA); offshoots from these veins at 60° to vein itself.	1			1	1	
80		24.38	28.96	Qtz veins (milky) every 10 cm or less, and are parallel to bedding, but a few (~5%) are narrow and 130° to CA (Bedding at 45 deg), Sulphides concentrated at margins of quartz, evidence of motion across veins.	1			1	1	
80		28.96	30.48	Limonite staining on irregular fracture faces is bright orange; Quartz-rich section toward bottom of sample, heavy carbonate alteration creates crumbly white clay to sand texture in 10 cm section at 20° to CA.	1			1	2	
80		30.48	36.58	Silicified MSED; Quartz-rich from large and numerous veins - 90% parallel to metased bedding	1			1	1	
10	36.58 - 192.02	36.58	41.15	GND; contact not seen as recovery is poor and core is v broken up. Lim stained on numerous microfracts and throughout matrix of GND; color is orange-brown with GND texture showing through. White calcite on fracture faces; to 41.15m very broken core, with ave size 2.5cm in diameter.	3			1	2	
10		41.15	43.80	More competent; Regular fractures at 50° and 110° to CA; Avg size 8cm long; limonite still pervasive.	3			1	2	
10		43.80	47.24	Very broken core; Limonite pervasive with calcite on fracture faces; Crumbly clay to sandy texture. From 45.52 to 45.65m carbonate is pervasive (white crumbly texture).	4			1	2	
10		47.24	50.29	V. poor recovery (21-25%), crumbly, carb and lim sand with remnant GND, qtz eyes, and GND pieces, largest 3cm.						
10		50.29	51.82	More competent GND with texture; Limonite near pervasive; so occasional pale orange brown color permeates	2			1	1	
10		51.82	53.34	Similar to above but with quartz veins/sulphide veins						
10		53.34	54.86	GND very broken up with limonite precipitated on fractures (and micro-fracts); Most have calcite crystallization as well, up to 2mm thick on larger faces.	2	1	1	1	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.5	1.0			0.0				3.0								4.0				B292215	14.02	15.24	<0.005			VA05052412	1.22
																						B292216	BLANK		<0.005			VA05052412	
1	1	4.0	4.0	50																		B292217	15.24	16.76	<0.005		Veins combine sulphide conc in carb/qtz vein.	VA05052412	1.52
1	3	1.5	1.5	5		1.0	q/cb	2	1	10.0			12.0					3.0	3.0										
6	3	3.0	8.0	40		1.0	q/cb	2		5.0								5.0				B292218	16.76	18.29	<0.005			VA05052412	1.53
							s	1																					
0																						B292219	18.29	19.51	<0.005			VA05052412	1.22
3	1	2.0	4.0	30		2.0				8.0								4.0				B292220	19.51	20.34	<0.005		Selvage includes banded layers around qtz and conc of ox-py.	VA05052412	0.83
0																						B292221	20.34	21.34	<0.005			VA05052412	1.00
0																						B292222	20.34	21.34	<0.005	DUP		VA05052412	1.00
4	1	1.0	4.0	80		0.0				8.0								4.0				B292223	21.34	22.86	<0.005		Some pieces	VA05052412	1.52
0																						B292224	22.86	24.38	<0.005			VA05052412	1.52
4	1	2.0	8.0	50		0.0				10.0								5.0				B292225	24.38	25.91	<0.005			VA05052412	1.53
7	1	5.0	13.0	55		3.0	q	2		10.0								5.0				B292226	25.91	27.43	<0.005			VA05052412	1.52
8	1	6.0	24.0	50		10.0	q	2		12.0								5.0				B292227	27.43	28.96	<0.005		mechanical alt'n (breakage) = 3	VA05052412	1.53
6	1	12.0	18.0	60		10.0	q	2		15.0								5.0				B292228	28.96	30.48	<0.005		m=3	VA05052412	1.52
6	1	12.0	18.0	60		10.0	q	2		15.0								5.0				B292229	28.96	30.48	<0.005	PD/CA		VA05052412	1.52
																						B292230	STANDARD 5E		1.405	5E		VA05052412	
3	1	5.0	7.0	50		2.0	q	4	1	10.0								5.0				B292231	30.48	32.00	0.005			VA05052412	1.52
9	1	6.0	15.0	55	30		q	4		1.0								5.0				B292232	32.00	33.53	<0.005			VA05052412	1.53
20	1	6.0	80.0	90	60	0.0				20.0								5.0				B292233	33.53	35.05	<0.005			VA05052412	1.52
4	1	2.0	8.0	50		0.0				5.0								5.0				B292234	35.05	36.58	0.008			VA05052412	1.53
0																						B292235	36.58	38.10	0.05			VA05052412	1.52
																						B292236	BLANK		<0.005			VA05052412	
0																						B292237	38.10	39.62	0.047			VA05052412	1.52
8	1	1.0	8.0	55	45	3.0	q	5	2	2.0			2.0					4.0	0.0			B292238	39.62	41.15	0.173			VA05052412	1.53
4	1	1.5	4.5	45		3.0	q	3	2	2.0	1.0		20.0					5.0	0.0			B292239	41.15	42.67	0.159			VA05052412	1.52
0																						B292240	42.67	44.20	0.083			VA05052412	1.53
5	1	2.0	6.0	35		1.0	q	3	1	0.1									0.0			B292241	44.20	45.72	0.017			VA05052412	1.52
5	1	2.0	6.0	35		1.0	q	3	1	0.1									0.0			B292242	44.20	45.72	0.016	DUP		VA05052412	1.52
0																						B292243	45.72	47.24	0.035			VA05052412	1.52
0																						B292244	47.24	48.77	0.018			VA05052412	1.53
0																						B292245	48.77	50.29	0.108			VA05052412	1.52
0																						B292246	50.29	51.82	0.042			VA05052412	1.53
2	6	0.3	0.3	70	150	1.0	q	3	2	40.0			60.0					4.0	1.0										
1	1	0.5	0.5	25		5.0	q	2	2	1.0								5.0											
							chl	1																					
1	1	4.0	4.0	0		0.0				0.0												B292247	51.82	53.34	0.058			VA05052412	1.52
2	1	2.0	3.0	50			q	2	2	3.0								5.0				B292248	53.34	54.86	0.11			VA05052412	1.52
							s/chl/cb	1																					

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 3 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		54.86	56.39	Microfractures/veins at 2 angles: 30° and 150° to CA						
10		56.39	57.91	Alt'd GND continues						
10		57.91	59.44	Xenolith (amphibolite, f-grained) 3cm by 3cm at 58.20m.						
10		59.44	60.96	95% loss of core (5% rec); Crumbly with one calcite vein; Chlorite alteration on fracture faces						
10		60.96	64.01	Alt'd GND continues	2	1	1	1	2	
10		64.01	65.53	More altered GND due to increased shear action (mechanical alteration); Qtz eyes in carb-lim rich weakened but competent core.	2	1	1	1	2	
10		65.53	67.07	Veinlets continue to indicate mechanical action and shear for 1st metre; Followed by silicified section (hard - nail won't scratch it, GND texture faded). Sphalerite seen; opaque black; tabular, hard						
10		67.07	68.58	Very broken core with poor recovery (47%)	4	1	1	1	2	
10		68.58	70.10	Strong limonization of GND wi limonitic quartz veins with sphalerite and minor aspy; one unaltered section from 68.9 to 69.2m (between veinlets)	3	1	1	1	2	
10		70.10	73.15	Small areas of unaltered GND; Max 15cm long between fractures and microveinlets of limonite and calcite (to 79.25m)	2	1	1		2	
10		73.15	79.25	Sericite slickenslides are seen on regular fractures at 40° to CA; Sphalerite appears as 2-3mm (max) angular black mineral in middle of vein, associated with cpy and aspy (attached to diff grains of sph); Aspy also disseminated in selvage of veins.	2	1	1		2	
				1cm massive aspy vein at 76.54m; aspy (90%) with calcite (10%); Slickensides still at 76.61m; dendritic growth of biotite on surface overtop of slickenslides						
10		79.25	85.29	Limonized and carbonitized GND; original texture still visible (qtz, bt, etc); but matrix highly carb-rich (yellowish-white) and oxidized powdery limonite (orangey-brown) infiltrates the rock with >1cm selvages.	2	1	1		2	
10		85.29	85.67	Light grey unaltered GND with one qtz-carb vein at low angle	1				1	
10		85.67	86.95	Limonite + carbonate alteration pervasive; Weak, crumbly rock; coarse sand makes up 40% of sample; Max size: 10cm lengths. Color: deep greenish brown with yellowish white patches in coherent pieces	4	2	1	1	3	
10		86.95	88.39	Highly altered to extremely altered. SHEAR ZONE (mechanical alt'n a factor). Quartz eyes visible btwn dark brown-black fine laminations with movement indicators; Sericite slickenslides well developed on planes at 55° to CA; Shear foliation at 80-85° to CA; Gouge clay last 12cm of sample	4	1	1	1	2	
10		88.39	92.96	Crumbly soft rock to sand-size fragmented GND; 90% stained by limonite and carbonate; Colour is med brown; Weak slickensides pronounced in minor sericite, parallel to long axis of fracture face at 55° to CA.	3	1	1	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	2.0	3.0	50			q	2	2	3.0								5.0				B292249	53.34	54.86	0.107	PD/CA		VA05052412	1.52
							s/chl/cb	1																				
																						B292250	STANDARD 2B		3.04	2B		VA05052412	
																						B292251	54.86	56.39	0.033			VA05052412	1.53
0																						B292252	56.39	57.91	0.057			VA05052412	1.52
3	1	2.0	4.0	10		1.0	q	3	0	0.0												B292253	57.91	59.44	0.142			VA05052412	1.53
1	1	0.5	0.5	10		1.0	q	4	1				1.0									B292254	59.44	60.96	0.168		Carbon broken piece	VA05052412	1.52
1	4	0.5	0.5				cb	3	2	0.0												B292255	60.96	62.48	0.046			VA05052412	1.52
3	1	1.5	4.0	30	50	0.5	q	1	2	5.0	1.0							5.0				B292256	BLANK		<0.005			VA05052412	
																						B292257	62.48	64.01	0.062			VA05052412	1.53
2	1	1.0	2.0	50		0.5	q	1	2	1.0								5.0				B292258	64.01	65.53	0.086			VA05052412	1.52
																						B292259	65.53	67.07	0.11			VA05052412	1.54
2	1	0.5	1.0	25	30	1.0	q/chl	1	2						10.0							B292260	67.07	68.58	0.121			VA05052412	1.51
1	1	1.0	1.0	20		1.0	q	2	1																				
							cb	1														B292261	68.58	70.10	0.268			VA05052412	1.52
3	1	1.0	3.0	25		4.0	q	2	3				1.0		5.0				3.0										
							cb/chl	1														B292262	68.58	70.10	0.125	DUP		VA05052412	1.52
3	1	1.0	3.0	25		4.0	q	2	3				1.0		5.0				3.0										
							cb/chl	1														B292263	70.10	71.63	0.11			VA05052412	1.53
3	1	4.0	8.0	45		2.0	q	3	2				1.0																
							chl	1														B292264	71.63	73.15	0.02			VA05052412	1.52
2	1	1.0	2.0	35		1.5	q	3	2		4.0							2.0											
							chl	1														B292265	73.15	74.68	0.151			VA05052412	1.53
3	1	1.0	2.0	25		3.0	q	3	1			1.0	2.0		8.0														
							s/chl	1														B292266	74.68	76.20	0.029			VA05052412	1.52
1	1	1.0	1.0	25		6.0	q	3					3.0		2.0														
							chl	4																					
							cb	2																					
1	6	1.0	1.0	40		0.0			1				90.0					1.0				B292267	76.20	77.72	0.06		1 cm massive aspy vn	VA05052412	1.52
1	1	1.0	1.0	25		6.0	chl	4																					
							q/cb	2																					
1	4	1.0	1.0	45							30.0							5.0				B292268	77.72	79.25	0.034			VA05052412	1.53
1	1	1.0	1.0	25							5.0																		
1	4	1.0	1.0	45							30.0							5.0				B292269	77.72	79.25	0.035	PD/CA		VA05052412	1.53
1	1	1.0	1.0	25							5.0																		
																						B292270	STANDARD 6F		2.81	6F		VA05052412	
0																						B292271	79.25	80.77	0.035			VA05052412	1.52
1	1	2.0	2.0	30		8.0	q	2			10.0		1.0					4.0				B292272	80.77	82.30	0.088			VA05052412	1.53
							chl	3																					
0																						B292273	82.30	83.82	0.016			VA05052412	1.52
2	1	3.0	5.0	40		5.0	q	2	1	5.0	2.0							5.0				B292274	83.82	85.29	0.053			VA05052412	1.47
							chl	1																					
1	3	1.0	1.0	8		0.0				8.0	1.0							5.0				B292275	85.29	85.67	0.116			VA05052412	0.38
																						B292276	BLANK		<0.005			VA05052412	
0																						B292277	85.67	86.95	0.096			VA05052412	1.28
1	3	2.0	2.0	50		0.0				0.1								5.0				B292278	86.95	88.39	0.085			VA05052412	1.44
1	1	1.0	1.0	10		3.0	chl	2	1	0.0												B292279	88.39	89.92	<0.005			VA05052412	1.53

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 5 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION: From → To:	From:	To:	Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		92.96	93.61	Light brown clay dominates this sample (70%) plus quartz eyes and a few <3cm GND (highly altered) chunks.	3	1		3	1	
10		93.61	96.62	Carbonate and limonite altered GND; Pervasive through veinlets and matrix; Crumbly and very broken up.	3	1		1	2	
10		96.62	96.82	Aphanitic; GND texture erased to dark grey/dark green; chloritic and oxidized (sulphides?) and limonite pervasive	4	2	3		2	
10		96.82	99.95	GND s at 93.61-96.63m above, with slightly more sericite	3	2		1	2	
10		99.95	101.13	Highly altered GND. Calcite throughout veinlets and forming large areas. 100% clay to gravelly texture.	4	3	1	2	3	
10		101.13	109.30	Limonite and carbonate altered GND (crumbly and weak core); lim/carb pervasive through veinlets and matrix. Overall colour is whitish brown. Regular low-angle limonite-covered fractures (20°); Weak slickenslides at 108.7m in sericite/chlorite on face @30° to CA.	3	2	1	1	2	
10		109.30	110.65	Zone of extreme alteration surrounding a 2cm calcite vein with alteration to clay in 20cm selvage; Surrounding clay is very altered but competent core; GND texture totally erased to dark green-blue grey, with a matte lustre for 20cm beyond either edge of clay; Extreme edges are yellowish brown from pervasive limonite and calcite throughout core.	3	3	1	2	3	
10		110.65	111.80	GND texture returns, but is infused with limonite and calcite; crumbly texture around	2	1	1	1	2	
10		111.80	114.87	Unaltered GND separated by qtz veins and their selvages; Also microfractures infilled with limonite with tiny (0.5cm) selvages, brown and oxidized; Occurrence ~5 per 20cm (minimum); Weak slickensides on fracture face in calcite/limonite at 30° to CA; Slicks at 30° to CA.	1		1		1	
10		114.87	117.60	Section is very altered; Dark blue-green grey with 1cm-5cm limonized selvages around microfractres; Dull appearance; GND texture erased; Competent core; 100% recovery here.	3	3	2	0	2	
10		117.60	122.65	Unaltered GND except selvages around qtz veins and limonite-covered microfractures; Low angle microfracture faces show slickenslides in chlorite, limonite.	1		1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B292280	89.92	91.44	0.022			VA05052412	1.52
0																						B292281	91.44	92.96	0.018			VA05052412	1.52
0																						B292282	91.44	92.96	0.023	DUP		VA05052412	1.52
0																						B292283	92.96	93.61	0.042			VA05052412	0.65
0																						B292284	93.61	94.49	0.126			VA05052412	0.88
4	1	1.5	4.0	30	60	4.0	q	3	2	5.0					5.0			5.0				B292285	94.49	95.59	0.043		Sulphides in high angle vein	VA05052412	1.10
1	1	1.0	1.0	50		2.0	q	1	2	1.0								5.0				B292286	95.59	96.62	0.115			VA05052412	1.03
							cb	2																					
0																						B292287	96.62	96.82	0.015			VA05052412	0.20
0																						B292288	96.82	97.54	0.04			VA05052412	0.72
0																						B292289	96.82	97.54	0.034	PD/CA		VA05052412	0.72
																						B292290	STANDARD 7G		4.61	7G		VA05052412	
2	1	1.5	3.0	60	50	1.0	q	1	3	2.0			1.0		2.0			5.0	2.0			B292291	97.54	99.06	0.042			VA05052412	1.52
							s	2																					
1	3	1.5	1.5	60		0.5	cb/q	1	2	5.0								5.0				B292292	99.06	99.95	0.036			VA05052412	0.89
1	6	0.8	0.8	60		6.0	cb	4	4				100.0					5.0				B292293	99.95	100.58	0.278			VA05052412	0.63
0																						B292294	100.58	101.13	0.068			VA05052412	0.55
1	1	1.0	1.0	40		2.0	chl/q	2	2	1.0								5.0				B292295	101.13	102.11	0.025			VA05052412	0.98
																						B292296	BLANK		<0.005			VA05052412	
2	3	1.5	2.5	40		10.0	chl/q	2	4						2.0			5.0				B292297	102.11	103.63	0.034			VA05052412	1.52
5	3	1.5	6.0	40		4.0	q/chl	2	2	0.0												B292298	103.63	105.16	0.023			VA05052412	1.53
0																						B292299	105.16	106.68	0.029			VA05052412	1.52
2	3	1.0	2.0	35		6.0	q	1	1				15.0						2.0			B292300	106.68	108.00	0.074			VA05052412	1.32
							cb	3																					
2	1	1.2	2.4	35	50	2.0	q	2	1	3.0			2.0					4.0	2.0			B292301	108.00	109.30	0.105			VA05052412	1.30
2	1	1.2	2.4	35	50	2.0	q	2	1	3.0			2.0					4.0	2.0			B292302	108.00	109.30	0.104	DUP		VA05052412	1.30
1	4	1.5	1.5	20		135.0	cb/s	3	4													B292303	109.30	110.65	0.086			VA05052412	1.35
							chl	1																					
1	1	3.0	3.0			40.0	cb	3	4	2.0								4.0				B292304	110.65	111.80	0.022		Grey qtz	VA05052412	1.15
							q	2																					
							chl	1																					
5	1	4.0	12.0			3.0	q/cb	2	2	3.0					5.0			4.0				B292305	111.80	112.78	0.036			VA05052412	0.98
1	1	4.0	4.0	10		0.0							1.0					3.0				B292306	112.78	113.40	0.026			VA05052412	0.62
2	1	2.0	4.0	60		1.0	q	3	2			1.0	6.0		3.0			2.0	4.0			B292307	113.40	114.87	0.267			VA05052412	1.47
							cb	1																					
3	3	0.5	1.5	30		3.0	q/cb	3	1			1.0	5.0		3.0			1.0	1.0										
2	6	0.5	1.0	30		2.0			3	40.0	0.1		40.0				20.0					B292308	114.87	116.41	0.118		other' is hematite	VA05052412	1.54
2	6	0.5	1.0	30		2.0			3	40.0	0.1		40.0				20.0					B292309	114.87	116.41	0.115	PD/CA	other' is hematite	VA05052412	1.54
																						B292310	STANDARD 6F		2.8	6F		VA05052412	
2	1	1.5	3.0	50		4.0	q/cb	2	3	15.0								3.0				B292311	116.41	117.60	0.142			VA05052412	1.19
							s/chl	1																					
3	6	1.3	3.5	45		5.0	q/cb	2	3	100.0								3.0											
							s/chl	1																					
3	1	3.0	6.0	35		2.0	q	3	1	2.0	8.0	0.1	2.0					2.0				B292312	117.60	118.87	1.52			VA05052412	1.27
							chl	1																					
2	4	0.4	0.8	25		4.0	q/chl	2	2	0.0												B292313	118.87	120.40	0.277			VA05052412	1.53
2	1	2.5	4.5	25		8.0	q	1	3	5.0					7.0			4.0											

DRILL LOG LEGEND P1 | DATE: 16-19-Jun-05 | PAGE 7 of 12

DRILL HOLE # : DG05-285C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		122.65	126.77	Minor altered GND; Veinlets of limonite and calcite pervasive; Max length of unaltered GND is 20cm; Weak slickenslides on low angle (10° to CA) fracture faces	2			1	2	
10		126.77	133.40	Very minor altered GND; Straight grey quartz veins with small selvages (@30-40°) are intersected by one quartz/carb vein with dramatic selvage (irregular and carb-rich); both sets contain po. At intersections po concentrated, up to 50%	1				1	
10		133.40	136.38	Unaltered GND except wide selvages around qtz veins; Very minor limonite on microfractures	1	1	1		1	
10		136.38	150.88	Unaltered GND except narrow selvages adjacent to qtz and qtz-carb veins; Very minor limonite on microfractures; Calcite concentrated on microfractures as well, up to 0.2cm; At 144.42m, wispy veins of calcite and ox'd py extend through unaltered GND; Angle to CA is 20°	1	1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

PAGE 8 of 12

094878

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval					
						Selvages				Sulphides									Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	2																					
3	1	1.5	3.5	70		2.0	q	4	0				1.0		10.0			3.0	2.0			B292314	120.40	121.92	0.29		sph max 10%, min 1%	VA05052412	1.52
							cb	2																					
1	1	1.0	1.0	25		0.5	cb/chl	2	1						3.0			1.0				B292315	121.92	122.65	0.019			VA05052412	0.73
							q	1																					
1	3	1.5	1.5	30		1.0	q/chl	1	1		2.0		8.0					0.0	0.0										
							cb	2																					
																						B292316	BLANK		<0.005			VA05052412	
1	1	3.0	3.0	45		3.0	q/cb	2	2						2.0			2.0				B292317	122.65	123.44	0.181			VA05052412	0.79
1	1	1.0	1.0	30		2.0	q	3	0						1.0			4.0				B292318	123.44	124.97	0.044			VA05052412	1.53
1	4	0.5	0.5	10		2.0	cb	2	4	0.0																			
1	6	0.6	0.6	35		4.0	s	2	1	40.0								3.0				B292319	124.97	125.44	0.077			VA05052412	0.47
							cb	4																					
2	1	1.5	3.0	35		0.5	q	3	3		3.0		5.0					3.0	1.0			B292320	125.44	126.77	0.026			VA05052412	1.33
3	1	1.0	2.0	40	30	2.0	q/cb	3	0		10.0							1.0				B292321	126.77	128.02	0.029			VA05052412	1.25
1	3	0.5	0.5	150		4.0	q	2	1	5.0	5.0							3.0											
							cb	5																					
1	3	0.5	0.5	150		4.0	q	2	1	5.0	5.0							3.0				B292322	126.77	128.02	<0.005	DUP		VA05052412	1.25
							cb	5																					
3	1	2.0	9.0	25		2.0	q	1	1	0.0												B292323	128.02	129.54	0.021			VA05052412	1.52
							cb	3																					
4	1	2.0	6.0	45	30	2.0	q/chl	2			8.0							5.0				B292324	129.54	131.86	0.04			VA05052412	2.32
3	1	1.5	4.5	50		4.0	q	3	1	2.0	2.0							5.0				B292325	131.86	132.59	0.063			VA05052412	0.73
1	6	1.5	1.5	50		10.0	q/chl	3	1	100.0								4.0											
0																						B292326	132.59	133.40	0.053			VA05052412	0.81
4	1	3.0	7.0	25		20.0	q/s/cb	2	1	5.0	2.0							2.0				B292327	133.40	134.46	0.095			VA05052412	1.06
							chl	1																					
1	1	2.0	2.0	45		1.0	q/s/cb	2	0				2.0						1.0			B292328	134.46	135.64	0.043			VA05052412	1.18
							chl	1																					
1	1	2.0	2.0	45		1.0	q/chl	2	0				2.0						1.0			B292329	134.46	135.64	0.055	PD/CA		VA05052412	1.18
							chl	1																					
																						B292330	STANDARD 1A		0.872	1A		VA05052412	
3	1	1.0	3.0	40		0.0							2.0						1.0			B292331	135.64	136.38	0.06			VA05052412	0.74
1	3	1.5	1.5	45		2.0	q	3	0	3.0								2.0				B292332	136.38	137.16	0.031			VA05052412	0.78
							s	2																					
1	1	1.0	1.0	45		0.0				2.0								5.0				B292333	137.16	138.68	0.689			VA05052412	1.52
1	3	1.0	1.0	45		6.0	q/cb/s	1	0	5.0			5.0					4.0											
							chl	4																					
3	1	1.0	3.0	45		2.0	q/cb	2	0				2.0					5.0				B292334	138.68	140.21	0.121			VA05052412	1.53
2	3	0.5	1.0	50		6.0	q/cb	3	0	3.0	3.0							4.0				B292335	140.21	141.73	0.067			VA05052412	1.52
							chl	4																					
							s	2																					
1	1	1.0	1.0	20		4.0	q	4			5.0																		
							s	1																					
																						B292336	BLANK		<0.005			VA05052412	
4	1	0.5	2.0	40		1.0	q	4	0		4.0							1.0				B292337	141.73	143.26	0.409			VA05052412	1.53
							s	1																					
1	1	0.5	0.5	35		0.0				8.0								5.0				B292338	143.26	144.78	<0.005			VA05052412	1.52
2	1	1.0	2.0	35		1.0	q	3			5.0		1.0					2.0	1.0			B292339	144.78	146.30	0.012			VA05052412	1.52
							s	2																					
2	4	0.4	0.8	30		1.0	q	3					5.0						3.0										
							cb/s	2																					

DRILL LOG LEGEND P1	DATE: 16-19-Jun-05	PAGE 4 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		150.88	163.07	Unaltered GND with fewer number of qtz vns and smaller selvages		1	1		1	
10		163.07	170.69	Unaltered GND. Calcite slightly more prevalent; So core not as competent; Calcite up to 0.2cm thick on broken faces		1			1	
10		170.69	178.31			2	1		1	
10		178.31	179.12	Chloritized zone for 65cm; GND texture erased; One small qtz vein seen in centre; Py totally oxidized in clay seams.	1	1	3	1	1	
10		179.12	192.02	Unaltered GND with quartz veins to EOH		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar,, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	1																					
2	1	1.0	2.0	40		1.0	q	2			15.0											B292340	146.30	147.83	0.07			VA05052412	1.53
							chl	1																					
2	3	0.5	1.0	30		3.0	q	2		5.0	1.0							1.0											
							cb	4																					
6	1	1.5	45.0	50		12.0	q/chl	2	0		10.0							1.0				B292341	147.83	149.35	0.224			VA05052412	1.52
							cb	4																					
							s	1																					
6	1	1.5	45.0	50		12.0	q/chl	2	0		10.0							1.0				B292342	147.83	149.35	0.077	DUP		VA05052412	1.52
							cb	4																					
							s	1																					
2	1	1.5	2.0	40		8.0	q/chl	2	0		8.0							0.0				B292343	149.35	150.88	0.014			VA05052412	1.53
							cb	4																					
							s	1																					
7	1	2.0	6.0	25	40	1.0	q	2			10.0		0.1									B292344	150.88	152.40	0.048			VA05052412	1.52
1	1	8.0	8.0	35		1.0	q	3		2.0								5.0											
2	1	6.0	10.0	10		2.0	q	3	0	4.0			1.0		2.0			2.0	2.0			B292345	152.40	153.92	0.037			VA05052412	1.52
3	1	8.0	10.0	35	70	2.0	q	3	0		10.0							1.0				B292346	153.92	155.45	0.209			VA05052412	1.53
2	1	1.0	2.0	30		4.0	q/cb	2					2.0									B292347	155.45	156.97	0.026			VA05052412	1.52
							chl	1																					
0																						B292348	156.97	158.50	0.017			VA05052412	1.53
0																						B292349	156.97	158.50	0.029	PD/CA		VA05052412	1.53
																						B292350	STANDARD 5E		1.405	5E		VA05052412	
4	1	1.0	4.0	15	50	1.0	q	3	0		3.0		5.0					0.0	4.0			B292351	158.50	160.02	0.035			VA05052412	1.52
							chl	1																					
3	1	1.5	3.0	35		1.0	q	3	0		7.0							1.0				B292352	160.02	161.54	0.033			VA05052412	1.52
							s/chl/cb	1																					
2	1	1.5	2.5	50		1.0	q	3	0		5.0							1.0				B292353	161.54	163.07	0.071			VA05052412	1.53
							s/chl/cb	1																					
4	1	0.5	1.0	40	30	1.0	q	3	0				10.0									B292354	163.07	164.59	0.242			VA05052412	1.52
							chl	2																					
3	1	1.0	2.0	50	30	1.0	q	3	0		15.0		5.0									B292355	164.59	166.12	0.036			VA05052412	1.53
							chl	2																					
																						B292356	BLANK		<0.005			VA05052412	
1	3	4.0	4.0	40		6.0	q	2	0		3.0	1.0						2.0	4.0			B292357	166.12	167.64	1.445			VA05052412	1.52
							chl	4																					
3	1	0.5	1.5	30	35	1.0	q	3	0		5.0							5.0				B292358	167.64	169.16	0.084			VA05052412	1.52
1	1	1.0	1.0	30		2.0	q/cb	2	0	2.0	2.0							5.0				B292359	169.16	170.69	0.022			VA05052412	1.53
							chl	1																					
4	1	1.0	4.0	35		5.0	q/chl/s	2			10.0	1.0										B292360	170.69	172.21	0.023			VA05052412	1.52
							cb	1																					
0																						B292361	172.21	173.74	0.02			VA05052412	1.53
0																						B292362	172.21	173.74	0.018	DUP		VA05052412	1.53
2	1	1.3	2.5	30		1.0	q	3			2.0											B292363	173.74	175.26	0.041		Grey Quartz	VA05052412	1.52
1	1	1.0	1.0	15		4.0	q	2			2.0																		
							chl/cb	1																					
5	1	1.2	4.0	35	15	1.0	q/chl	2			5.0											B292364	175.26	176.78	0.02		Grey Quartz	VA05052412	1.52
							cb	1																					
2	1	0.5	1.0	60	50	2.0	chl	3	1													B292365	176.78	178.31	0.1			VA05052412	1.53
2	1	0.5	1.0	30	60	65.0	chl	3	1	20.0								5.0				B292366	178.31	179.12	0.068			VA05052412	0.81
							s	1																					
2	1	0.5	1.0	50		2.0	q	3		2.0								1.0				B292367	179.12	179.83	0.023			VA05052412	0.71
							chl	2																					
5	1	1.5	5.2	60	30	4.0	q	3			5.0							0.0				B292368	179.83	181.36	0.053			VA05052412	1.53
							cb	1																					

DRILL LOG LEGEND — P1	DATE: 16-19-Jun-05	PAGE 11 of 12	
DRILL HOLE # : DG05-285C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 16-19th, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	1.5	0.2	60	30	4.0	q/cb	3			5.0							0.0				B292369	179.83	181.36	**0.131**	PD/CA		VA05052412	1.53
							cb	1																					
																						B292370	STANDARD 4D		**0.433**	4D		VA05052412	
6	1	1.0	4.0	60	30	1.0	q	3			8.0											B292371	181.36	182.88	**0.192**			VA05052412	1.52
							cb	2																					
							chl	1																					
2	1	0.5	1.0	25		1.0	q	3	0		6.0							1.0				B292372	182.88	184.40	**0.014**			VA05052412	1.52
							s	1																					
7	1	1.0	5.0	40		1.0	q	3	0		5.0							1.0				B292373	184.40	185.93	**0.128**			VA05052412	1.53
							s	1																					
5	1	1.0	4.0	45		1.0	q/s	4	0		3.0		5.0					1.0	4.0			B292374	185.93	187.45	**0.02**			VA05052412	1.52
5	1	1.0	3.0	40		3.0	q	3														B292375	187.45	188.98	**0.065**			VA05052412	1.53
							s/chl/cb	2																					
																						B292376	BLANK		**<0.005**			VA05052412	
4	1	2.0	3.5	50	40	1.5	q	3	0	1.0	6.0	0.1	5.0					0.0	1.0			B292377	188.98	190.50	**0.048**			VA05052412	1.52
							cb	2																					
							chl	1																					
4	1	0.5	2.0	50	40	1.0	q	3	0	3.0	10.0		7.0					1.0	0.0			B292378	190.50	192.02	**0.075**			VA05052412	1.52
							s/chl	1																E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-286C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 894m

BEARING: 000 | DIP: -50°

DATE STARTED: 18-Jun-05 | DATE COMPLETED: 20-Jun-05

LOGGED BY: Terry Croteau & Tom Patchell

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459209 NORTHING: 7099284

COORD SYSTEM: NAD 83: EASTING: 459091 NORTHING: 7099469

NAD 27 (CORRECTED for historic grid): EASTING: 459179 NORTHING: 7099294

SECTION LINE(historic grid): 459179

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 22.86

Deviation:

Casing: 22.86

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B380307 - B380385

Requisition #: MASP448STRGOL.05Q | Date Shipped: 24-June-05

Lab Record #: VA05053956 | Date Received: 5-July-05

Sample Sequence: B380386 - B380442

Requisition #: MASP448STRGOL.05Q | Date Shipped: 26-July-05

Lab Record #: VA05055093 | Date Received: 7-July-05

Duplicates:	B380322, B380342, B380362, B380382, B380402, B380422, B380442
Preparation Duplicate/ Check Assay:	B380309, B380329, B380349, B380369, B380389, B380409, B380429
Standards:	B380310 (7H), B380330 (4D), B380350 (3C), B380370 (1A), B380390 (4D), B380410 (3C), B380430 (5E)
Blanks:	B380316, B380336, B380356, B380376, B380416, B380436

FROM	TO	LITHOLOGY
22.86	59.64	GND
59.64	70.10	MSED (QZZ)
70.10	75.38	GND
75.38	106.10	MSED with GND Dykes
106.10	149.35	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
50.0	343.2	-50.5	009.2	010.2
100.0	344.7	-51.0	010.7	011.7
150.0	347.3	-51.3	013.3	014.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE of 8	
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-22.86			Casing (No Recovery)						
10	22.86-59.64m			GND (Main Interval). GND is highly altered to sericite/clay making modal composition difficult to interpret. Alteration trends to pervasive lim around 44m. 40% qtz, 20% kspar, 15% bt, 5% hbl.						
10		22.86	27.03	Altered GND, good recovery. Core shows significant alteration to sericite. 2cm massive sulphide veins at 25.12m, 25.18m, 26.13m, 26.48m, 26.52m. At 25.80m, 30cm gouge at 30° to CA terminates at sulphide vein. At 26.21m, 6cm gouge. Dissem py and aspy present to 27.03m.		4		2		
10		27.03	29.17	GND shows less alteration and less sulphides in veins, more competent. Diss aspy.		1		1		
10		29.17	30.48	GND is bleached, altered to ser. Sulphide veins present.		3				
10		30.48	33.63	GND unaltered, except for vein selvages. Core is broken, with decreased recovery as well as sulphide content.		1				
10		33.63	34.60	GND highly altered to clay. Disseminated aspy present. Sometimes concentrated on what appears to be fracture faces.						
10		34.60	34.85	25cm grey qtz vein with fractures filled w/ py; oxidized py on faces.						
10		34.85	44.01	Slightly altered GND w/ diss aspy found throughout. Veins reduce in size, frequency and sulphide content. Core becomes more broken; most gravel-sized at 41.15 to 44.01m. Slickensides present on weathered aspy at 41.65m.	1					
10		44.01	50.29	GND - Start of lim staining on fractures. Core recovery is still poor, core is broken, gravel-sized common. At 44.62m clay gouge, no contact. Aspy present on fractures at veins.	1					
10		50.29	51.82	GND. Limonite staining pervasive throughout sericite altered. Slightly bleached sulphides located on exterior of veins. Mafics removed where veins occur. Carb veinlets invade sporadically.	1	2				
10		51.82	53.34	GND. Slightly altered. Mafics visible. Sericite on fractures. Minor chlorite. Slickensides present on fractures. Qtz veins milky.	1	1				
10		53.34	56.39	Slightly limonized, competent GND. Carb veinlets pervasive. Aspy on fractures slickensided. @54.46m, clay gouge along frac at 80° to CA.	1	1	2	1	1	
10		56.39	57.91	Slightly altered GND, bleached sections with mafics altered to chlorite. @57.02m, GND changes to bleached with py/aspy (0.1-1%). Sulphide veinlets until end of interval.	1	1	3	1	2	
10		57.91	58.93	Slightly altered GND. Cb veinlets, slight lim staining. @57.91m, large quartz vein (4 cm?) with disseminated sulphides (aspy) @58.35m, sheeted qtz vein set (of 3) at 60 ° @58.93m, contact with fault gouge perpendicular to CA.	1		1	1	1	
10		58.93	59.64	Gouge zone, highly altered to clays. Little competency remains. Bleached white, crumbles easily. @59.64m, contact with MSED, no discernable angle		4	2	2		
80	59.64 - 70.10			QZZ metaseds, highly siliceous						
80		59.64	60.96	QZZ, limonized carb veinlets, lamination visible at 50°, 60° and 65° to CA. Clay (ser?) in frac	1			2		
80		60.96	62.48	Limonized QZZ, clay section @ 61.95m	1			1		

DRILL LOG LEGEND P2

8 Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotitie	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	6												20.0									B380307	22.86	24.38	0.087		too broken for measurements	VA05053956	1.52
2	1	0.5	0.5	75									3.0									B380308	24.38	25.13	0.192			VA05053956	0.75
2	1	0.5	0.5	75									3.0									B380309	24.38	25.13	0.201	PD/CA		VA05053956	0.75
																						B380310	STANDARD 7G		4.420	7G		VA05053956	
1	6	3.0	3.0	75						60.0								90.0				B380311	25.13	25.91	0.240			VA05053956	0.78
4	6	2.0	6.2	30						90.0								15.0				B380312	25.91	27.03	0.187			VA05053956	1.12
2	1	0.5	1.0	40						20.0			10.0									B380313	27.03	28.05	0.138			VA05053956	1.02
4	1	0.2	0.8	60									10.0									B380314	28.05	29.28	0.247			VA05053956	1.23
4	1	0.2	0.8	60									30.0									B380315	29.28	29.80	0.179			VA05053956	0.52
																						B380316	BLANK		<0.005			VA05053956	
5	1	0.2	1.0	60						20.0			10.0									B380317	29.80	30.48	0.276			VA05053956	0.68
1	1	0.5	0.5	60						5.0	3.0		2.0									B380318	30.48	32.00	0.145			VA05053956	1.52
4	1	0.5	1.2	60		5.0	q/chl	4	0				10.0									B380319	32.00	33.53	0.291			VA05053956	1.53
																						B380320	33.53	34.60	0.177			VA05053956	1.07
1	1	25.0	25.0							35.0												B380321	34.60	34.85	1.080			VA05053956	0.25
1	1	25.0	25.0							35.0												B380322	34.60	34.85	0.359	DUP		VA05053956	0.25
4	1	2.0	3.2	50									0.1									B380323	34.85	36.25	0.182			VA05053956	1.40
3	1	1.0	2.2	50		2.0	q/chl	3	0				10.0									B380324	36.25	37.58	0.354			VA05053956	1.33
2	1	0.2	0.4	80									5.0									B380325	37.58	39.08	0.181			VA05053956	1.50
1	1	0.2	0.2	60									0.1									B380326	39.08	40.58	0.132			VA05053956	1.50
4	1	0.2	0.8	60		5.0	q/s	3	0				10.0									B380327	40.58	42.08	0.180			VA05053956	1.50
1	1	0.2	0.2	70		3.0	q	3	0	1.0			3.0									B380328	42.08	43.58	0.165			VA05053956	1.50
1	1	0.2	0.2	70		3.0	q	3	0	1.0			3.0									B380329	42.08	43.58	0.179	PD/CA		VA05053956	1.50
																						B380330	STANDARD 4D		0.425	4D		VA05053956	
1	6	0.2	2.0	60									10.0					90.0				B380331	43.58	44.01	0.213			VA05053956	0.43
1	1	0.2	0.2	80									10.0									B380332	44.01	45.72	0.076			VA05053956	1.71
1	1	0.2	0.2	60									10.0									B380333	45.72	47.24	0.089			VA05053956	1.52
																						B380334	47.24	48.77	0.142			VA05053956	1.53
1	1	2.0	2.0	75		1	q	4	0				0.1									B380335	48.77	50.29	0.144			VA05053956	1.52
																						B380336	BLANK		<0.005			VA05053956	
5	1	2.5	4.5	70	50	5.0	q/cb	4					3.0									B380337	50.29	51.82	0.048			VA05053956	1.53
7	1	1.5	3.5	70		0.25	q	2		0.1								10.0				B380338	51.82	53.34	0.069			VA05053956	1.52
8	1	0.3	1.8	70		0.6				0.1												B380339	53.34	56.39	0.325			VA05053956	3.05
3	1	0.3	1.0	80		0.3	chl	3	2	2.0			2.0					1.0				B380340	56.39	57.02	0.212			VA05053956	0.63
4	6	0.2	0.8	65		0.2	q/chl	2	1	0.1			10.0					1.0	2.0										
2	1	0.2	0.4	50		0.4	chl			3.0								4.0				B380341	57.02	57.91	0.089			VA05053956	0.89
1	3	0.2	0.2	60																									
2	6	0.2	0.4	60		0.2	q/chl	2	1	40.0			60.0					20.0	5.0										
2	6	0.2	0.4	60		0.2	q/chl	2	1	40.0			60.0					20.0	5.0			B380342	57.02	57.91	0.109	DUP		VA05053956	0.89
2	1	0.2	0.4	50		0.4	chl			3.0								4.0											
1	3	0.2	0.2	60																									
8	1	0.4	3.0	60	90	0.3	chl	2	1				5.0					1.0				B380343	57.91	58.93	0.210			VA05053956	1.02
1	1	4.0	4.0	50		1.0	chl						15.0					1.0	5.0										
1	6	0.2	0.2	35		0.2	q	1	1				100									B380344	58.93	59.64	0.115			VA05053956	0.71
																						B380345	59.64	60.96	0.028			VA05053956	1.32
1	6	0.2	0.2	65						95.0			5.0					5.0				B380346	60.96	62.48	0.104			VA05053956	1.52

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE 3 of 8	
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		62.48	67.06	Slight limonitic colors (orange/brown). Core is broken; laminations visible on some whole pieces 30° to CA. Two small qtz veinlets x-cut bedding but no visible sulphides. Two 2cm qtz veins parallel bedding. In between 64.01-65.53m, qtz pieces show aspy, but no structure can be inferred.						
80		67.06	70.10	QZZ, grey with no lim. In pieces. Large qtz vein chunks visible (w/ trace aspy) but no visible measurement could be made. Section broken to gravel/cobble size. Poor recovery from 68.58 - > 70.10m.	0					
10	70.10-72.16	70.10	72.16	Highly altered GND. Bleached light green/white/off white. Milky qtz veins. Altered to clay. Py veinlet (<.2cm) 35° to CA. Sheeted qtz veins.10cm apart, 0.3cm thick at 50° to CA. @72.16m, contact with MSED at 60° to CA.						
80	72.16 - 72.61	72.16	72.61	MSED highly silicified, bleached whitish grey. Chloritized vein contact at 72.61m at 90° to CA.		1	1	1		
10	72.61 - 75.38	72.61	73.45	Highly clay altered GND. Bleached sericite rich, mafics present		4		2		
10		73.45	74.33	Highly chloritized GND - V. green colour, few mafics present			4		1	
10		74.33	75.38	Highly altered GND. Bleached white/green. No mafics present. Chalky, brittle but competent. Diss aspy found from 75.14 - 75.38m.		4	2	4	1	
80	75.38 - 78.53	75.38	76.20	MSED - Aspy in veinlets, 3 at 50° to CA. Parallel laminations. Highly silicified, clay altered.		2		3	1	
		76.20	78.53	Diss sulphides: 30% py. Parent rock MSED with high silicification. Foliation undulating. Cave in @ 77.72m. Small sulphide veinlets at 40° to CA, py on frac. Carb veinlets throughout.		1		1	1	
10	78.53-85.90	78.53	85.90	Highly altered GND. Bleached white/green, little to no mafics. Bt almost completely altered to chl. Speckled green color. At 82.73 - 83.47m, Small undulation of MSED bottom contact at 45-50° to CA.		1	4	1	1	
80	85.90-89.20	85.90	89.20	MSED: Regular qtz veins along foliation. Black, light grey banding. QZZ to phyllite. Small sections of GND visible (<10 cm typically, not throughout entire circumference of core). Foliation at 45- 65°. Qtz infilled in between foliation.	1	1	1			

DRILL LOG LEGEND P2

8 Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages			% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
									Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5 (0-5)	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	2.0	3.5	30		0.0															B380347	62.48	64.01	0.068			VA05053956	1.53
1	6	0.2	0.2									75.0									B380348	64.01	65.53	0.082			VA05053956	1.52
1	6	0.2	0.2									75.0									B380349	64.01	65.53	0.078	PD/CA		VA05053956	1.52
																					B380350	STANDARD 3C		0.089	3C		VA05053956	
																					B380351	65.53	67.06	0.014			VA05053956	1.53
																					B380352	67.06	68.58	0.015			VA05053956	1.52
									0.1												B380353	68.58	70.10	0.074		Relic quartz pieces	VA05053956	1.52
2	1	0.3	0.5	30	150	0.0			0.1												B380354	70.10	71.63	0.070			VA05053956	1.53
3	1	0.3	0.9	35		0.2	chl	2 1													B380355	71.63	72.16	0.046			VA05053956	0.53
																					B380356	BLANK		<0.005			VA05053956	
0																					B380357	72.16	72.61	0.016			VA05053956	0.45
3	1	0.5	1.0	80	60	3.0	chl	3	0.0												B380358	72.61	73.45	0.037			VA05053956	0.84
3	1	0.4	1.0	75		0.5	chl														B380359	73.45	74.33	0.049			VA05053956	0.88
																					B380360	74.33	75.14	0.028			VA05053956	0.81
1	6	0.2	0.2	70					5.0			95.0									B380361	75.14	75.38	0.006			VA05053956	0.24
1	1	0.2	0.2	70		0.2	chl	2 1																				
1	6	0.2	0.2	70					5.0			95.0									B380362	75.14	75.38	0.012	DUP		VA05053956	0.24
1	1	0.2	0.2	70		0.2	chl	2 1																				
1	1	0.5	0.5	50		0.2	q	1 1													B380363	75.38	76.20	0.012			VA05053956	0.82
2	1	0.3	0.6	60	30	0.2	s	1 1	0.0												B380364	76.20	77.72	0.046			VA05053956	1.52
3	6	0.2	0.6	30					95.0								60.0											
3	1	0.2	0.6	50					10.0			0.1									B380365	77.72	78.53	0.049			VA05053956	0.81
3	1	0.2	0.7	60		0.5	chl	4 2	10.0								80.0				B380366	78.53	78.92	0.038			VA05053956	0.39
							s	2																				
							q	1																				
1	1	0.4	0.4	60		1.0	chl	4				0.1									B380367	78.92	79.25	0.047			VA05053956	0.33
							s	2																				
3	1	1.5	1.5	55	75	0.5	chl	1 2													B380368	79.25	80.77	0.054			VA05053956	1.52
							s	3 1																				
3	1	1.5	1.5	55	75	0.5	chl	1 2													B380369	79.25	80.77	0.054	PD/CA		VA05053956	1.52
							s	3 1																				
																					B380370	STANDARD 1A		0.880	1A		VA05053956	
7	1	1.0	4.5	50		0.5	chl	1 1	5.0		10.0						4.0				B380371	80.77	81.47	0.021		max %'s py + aspy	VA05053956	0.70
1	6	0.6	0.6	65		0.3	q	1 1	90.0																			
1	6	0.2	0.2	50		0.0			50.0								80.0				B380372	81.47	82.30	0.030			VA05053956	0.83
4	1	0.4	1.5	45		1.0	chl	3 1	0.1			0.1																
							s	2																				
1	6	5.0	5.0	80					50.0			35.0					80.0				B380373	82.30	82.73	0.288			VA05053956	0.43
1	1	0.6	0.6	70		0.3	chl	1 1	25.0								90.0				B380374	82.73	83.47	0.026			VA05053956	0.74
6	1	1.2	3.0	55		0.4	chl	3 1	0.1			0.1					20.0				B380375	83.47	84.14	0.161			VA05053956	0.67
1	6	0.2	0.2	50		0.2	q	1 1	80.0			5.0																
																					B380376	BLANK		<0.005			VA05053956	
5	1	4.0	12.0	45	75							0.1									B380377	84.14	85.45	0.034			VA05053956	1.31
1	1	10.0	10.0			0.0			0.1			0.1																
1	1	0.6	0.6	60		0.3	5	3 0				0.1					2.0				B380378	85.45	85.90	0.037			VA05053956	0.45
1	6	0.5	0.5	50		0.0			50.0			10.0					90.0				B380379	85.90	86.87	0.010			VA05053956	0.97
12	1	2.0	13.0	50	110	1.0	chl	3	10.0			0.1					80.0									5-10% py		
1	3	0.2	0.2	20					2.0			0.1																
4	1	0.5	1.8	40	25	0.0			10.0												B380380	86.87	88.39	0.007			VA05053956	1.52
4	1	0.3	1.1	65		0.5	s	2 1													B380381	88.39	89.20	0.021			VA05053956	0.81
1	6	0.2	0.2	65					100.0								90.0											

DRILL LOG LEGEND P1	DATE: June 22-25, 2005	PAGE 5 of 8	
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	89.20-90.80	89.20	90.80	Small section of highly altered GND. Olive green colour. Few mafics. Slowly grades into MSED, starting @ 89.97m with xenoliths of MSED in GND. Veining sheeted, often paralleling laminations.	1	2	4	1	1	
80	90.80 - 99.06	90.80	91.54	MSED: Silicified. Some sections showing foliation @ 60° to CA. Sulphide vein at 91.22m.	1	2	1		2	
		91.54	94.90	Black, relatively unsilicified MSED. Planar foliations. Qtz not as infilled as above. Foliations at 30-40° to CA	1	1	1	2		
80		94.90	97.54	Slightly more silicified MSED. Foliations at 50° to CA where visible. Qtz infilled.	1	1		1	1	
		97.54	99.06	Darker MSED. Dark grey to black, some carbonate veinlets. Little silicification. @99.06m - contact w/ GND (fine grained) is @50°.	2	1			1	
11	99.06 -100.85	99.06	100.85	Speckled GND, yellowish tinge, to otherwise dark grey GND. Fine grained.	1	2	2	1		
80	00.85 - 103.4	100.85	103.47	MSED. Altered, silicified. Whitish green w/ abundant qtz infilling. Some weathering to clay w/ qtz eyes	2	2		1	1	
10	03.47 - 106.1	103.47	106.10	Dark grey to black GND. Few crystals visible. Some biotite and amphiboles but very dark colour. Many carb veinlets	2	1	1	1	1	
80	06.10 - 149.3	106.10	106.68	Highly altered MSED. Qtz invasive everywhere. Colour: green/light green w/ abundant carb veinlets	2	3	1	1	2	
80		106.68	108.20	MSED. Milky qtz veinlets spreading out randomly. Foliations @ 50° to CA. Sulphides cross cuts foliation.	3	1	1		1	
80		108.20	115.82	MSED, foliations at 50° alternating bands of light and black. Foliation often infilled with qtz. Broken, weathered section @ 112.20m. Pieces are angular and range from sand to pebble size.	1	1		1	2	
80		115.82	128.02	MSED altered to green color in few locations. @120.40m, S fold visible; perpendicular to core axis with chl band in middle. Many large qtz veins, but little visible mineralization. @119.07m, Cave in rubble; low angle predominant (<20°) carb veinlets. Qtz veins clear @123.44m, large aspy vein @ 126.49 - 127.84m, sulphides located on margins of small qtz veins, cross cutting MSEDS @ 20°-40° to CA opposite 50° MSED.	1	2	1		1	

DRILL LOG LEGEND P2

8 Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					Width (m)
1	6	0.2	0.2	65						100.0								90.0				B380382	88.39	89.20	0.013	DUP		VA05053956	0.81
4	6	0.2	0.8	40		1.2	s	3	1	40.0								20.0				B380383	89.20	90.80	0.027			VA05053956	1.60
							q	2																					
4	1	1.2	2.0	45		1.0	chl	2	1	2.0			1.0					10.0											
1	6	0.3	0.3	40		0.5	5	4		40.0			60.0					4.0				B380384	90.80	91.54	0.024			VA05053956	0.74
5	1	1.0	2.0	40	130					0.1			0.1					4.0											
3	1	1.0	2.5	50	30					0.1												B380385	91.54	92.96	0.008			VA05053956	1.42
1	6	0.2	0.2	50		0.6	q	4		20.0								4.0											
8	1	1.0	4.2	30	150	0.2	chl	1	1	5.0												B380386	92.96	94.49	0.024			VA05055093	1.53
3	6	0.2	0.6	50		11.0	q	5		20.0			15.0																
																						B380387	94.49	94.90	0.007			VA05055093	0.41
2	1	1.2	1.8	40		0.3	cb	3		0.0												B380388	94.90	96.01	0.007			VA05055093	1.11
2	1	1.2	1.8	40		0.3	cb	3		0.0												B380389	94.90	96.01	0.008	PD/CA		VA05055093	1.11
																						B380390	STANDARD 4D		0.418	4D		VA05055093	
5	1	2.2	7.0	50	150	0.5	q	3		5.0												B380391	96.01	97.54	0.041			VA05055093	1.53
							chl	1																					
3	1	0.8	1.4	60						10.0												B380392	97.54	99.06	0.038			VA05055093	1.52
3	1	3.1	6.8	60	20	0.2	q/chl	1		0.1			0.1					80.0				B380393	99.06	99.91	0.023			VA05055093	0.85
1	1	0.4	0.4	50		1.0	chl	3		1.0								5.0				B380394	99.91	100.85	0.023		Milky white qtz w/ py on margin	VA05055093	0.94
3	1	0.3	0.9	90	110	0.2	chl	1		5.0																			
2	1	3.0	3.9	70						20.0								60.0				B380395	100.85	102.11	0.008			VA05055093	1.26
1	1	0.9	0.9	45		0.2	s	1		25.0								40.0				B380396	102.11	103.47	0.012		Missed Blank; No Stamp	VA05055093	1.36
1	6	0.3	0.3	40		0.0				95.0								90.0											
0																						B380397	103.47	103.88	0.014			VA05055093	0.41
1	6	0.3	0.3	25		0.0				60.0								50.0				B380398	103.88	105.16	0.053			VA05055093	1.28
3	1	0.7	1.5	50	120	1.0	s/chl	2	1	2.0								10.0											
0																						B380399	105.16	106.10	0.075			VA05055093	0.94
3	1	1.0	3.0	50						15.0								10.0				B380400	106.10	106.68	0.029			VA05055093	0.58
1	1	2.5	7.5	65		0.0				0.0												B380401	106.68	108.20	0.018			VA05055093	1.52
1	6	0.2	0.2	40		3.2	q/chl/s	5		99.0			1.0																
1	6	0.2	0.2	40		3.2	q/chl/s	5		99.0			1.0									B380402	106.68	108.20	0.011	DUP		VA05055093	1.52
4	1	1.3	40.0	60	50	0.0				0.0												B380403	108.20	109.73	0.010			VA05055093	1.53
1	6	0.4	0.4	150		0.0				30.0								100.0											
1	1	1.0	1.0	40	0	0.2	s	2		0.0												B380404	109.73	111.25	0.019			VA05055093	1.52
1	6	0.4	0.4	40		0.5	s/chl	4		15.0			5.0					30.0											
1	1									0.0												B380405	111.25	112.78	0.064		Relic vein	VA05055093	1.53
2	1	4.0	6.0	50		0.2	chl	2		0.0												B380406	112.78	114.30	<0.005			VA05055093	1.52
2	1	0.2	0.4	40	25	0.2	chl	1		10.0								20.0				B380407	114.30	115.82	<0.005			VA05055093	1.52
4	1	9.0	18.0	65	50					0.1								30.0				B380408	115.82	117.35	0.007			VA05055093	1.53
4	1	9.0	18.0	65	50					0.1								30.0				B380409	115.82	117.35	0.008	PD/CA		VA05055093	1.53
																						B380410	STANDARD 3C		0.089	3C		VA05055093	
6	1	1.2	70.0	50	130																	B380411	117.35	118.87	<0.005			VA05055093	1.52
2	1	10.0	16.0	70	50	0.5	s/chl	2																					
5	1	3.5	7.0	50	150	0.3	chl	4														B380412	118.87	120.40	0.020			VA05055093	1.53
1	1	5.0	5.0	50		0.0				0.0												B380413	120.40	121.92	0.024			VA05055093	1.52
1	6	0.2	0.2	140						25.0			1.0																
2	6	0.5	0.9	150		0.0				30.0			3.0					15.0				B380414	121.92	123.44	0.017		Crosscuts foliation	VA05055093	1.52
3	1	10.0	21.0	50	150																								
1	6	0.3	0.3	150		1.2	s	4					80.0					40.0				B380415	123.44	123.71	0.039			VA05055093	0.27
																						B380416	BLANK		<0.005			VA05055093	

DRILL LOG LEGEND P1	DATE: June 22-25, 2005 PAGE 7 of 8		
DRILL HOLE # : **DG05-286C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMQN = 20; DIQR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		128.02	131.77	Clay gouge at start of interval.MSEDS are much more silicic with qtz invading between foliations and replacing entire sections (up to 15 cm wide). Qtz has green color while seds are dark grey/black. Foliations planar. Fracture planes along foliation still at 50° to CA. Qtz veins crosscut through foliation and infiltrate between. @131.06m - foliation undulating and ends abruptly, with clay and breccia at terminus.	1	1	3	1	2	
80		131.77	134.11	MSED more bleached, white/light grey/yellow tint with green colouration. Trace diss sulphides. Core broken to small cobbles. Qtz veinlets show selvage, often more visible than the veins. Seds are slightly steeper at 60° to CA	1	1			2	
80		134.11	138.20	MSEDS darker, less qtz, though still prevalent in between foliation. MSEDS darkening with depth, becoming speckled and some brown color showing.	2	3		1	1	
80		138.20	142.97	Bleached and highly fractured/weathered MSED. Color light green to white, rich in clay. Foliation barely visible. Foliations at 60-70° to CA @143.26m - Mislatch	2	5	3	2	2	
80		142.97	149.35	Black/white banded MSED. Silica rich with large section of quartz. Green tint hints at chlorite. Veins cross cut MSED. @148.25m, po veinlets very abundant.	1	1	2	1	1	
	EOH									

DRILL LOG LEGEND P2

8 Ox. State

0 = No Alteration 0 = No Oxidized Sulphides

5 = Intense Alt'n 5 = All Sulph Oxidized

Date: June 22-25, 2005

LOGGED BY: T. Patchell, T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
6	1	3.1	7.0	70	130	1.0	chl	5		10.0												B380417	123.71	124.92	0.005			VA05055093	1.21
1	6	0.3	0.3	40		0.0				40.0			2.0					30.0				B380418	124.92	126.49	<0.005			VA05055093	1.57
2	1	0.4	0.6	40	20	0.2	s	1		20.0			0.1					60.0				B380419	126.49	128.02	0.008			VA05055093	1.53
1	1	2.5	2.5	20		0.0				0.0												B380420	128.02	129.54	0.010			VA05055093	1.52
2	1	0.5	0.8	20		0.0				0.0												B380421	129.54	131.06	0.012			VA05055093	1.52
2	1	0.5	0.8	20		0.0				0.0												B380422	129.54	131.06	0.020	DUP		VA05055093	1.52
0																						B380423	131.06	131.77	<0.005			VA05055093	0.71
0																						B380424	131.77	132.59	<0.005			VA05055093	0.82
																						B380425	132.59	134.11	<0.005			VA05055093	1.52
1	1	0.4	0.4	140																		B380426	134.11	135.64	0.009			VA05055093	1.53
1	1	2.5	2.5	20		4.0	s/chl	4		15.0			0.1					50.0				B380427	135.64	137.16	<0.005			VA05055093	1.52
2	1	2.0	3.1	70						5.0												B380428	137.16	138.20	<0.005			VA05055093	1.04
1	6	0.4	0.4	130						20.0																			
1	6	0.4	0.4	130						20.0												B380429	137.16	138.20	<0.005	PD/CA		VA05055093	1.04
																						B380430	STANDARD 5E		1.470	5E		VA05055093	
0																						B380431	138.20	138.68	<0.005			VA05055093	0.48
1	6	0.3	0.3	150		0.0				5.0								95.0				B380432	138.68	140.21	0.010			VA05055093	1.53
3	1	1.2	3.2	55		0.5	chl	4		10.0												B380433	140.21	141.73	0.030			VA05055093	1.52
4	6	0.2	0.8	55	30	0.5	s/chl	2		40.0			20.0																
1	1									0.0												B380434	141.73	142.97	<0.005		Relict vein	VA05055093	1.24
1	6									30.0			5.0														Relict vein		
1	1	0.5	0.5	140		0.3	s	2		5.0												B380435	142.97	143.26	<0.005			VA05055093	0.29
																						B380436	BLANK		<0.005			VA05055093	
0																						B380437	143.26	144.78	<0.005			VA05055093	1.52
3	1	0.9	2.6	30	150	1.0	s/chl	5		0.1			0.1									B380438	144.78	146.20	0.009			VA05055093	1.42
1	1	15.0	15.0	60		5.0	chl	5		0.0												B380439	146.20	147.83	<0.005			VA05055093	1.63
1	1	0.5	0.5	130		0.0				10.0												B380440	147.83	148.44	0.154		Po veinlets	VA05055093	0.61
2	1	0.6	1.1	130		1.2	chl	4		20.0			1.0									B380441	148.44	149.35	0.006			VA05055093	0.91
2	1	0.6	1.1	130		1.2	chl	4		20.0			1.0									B380442	148.44	149.35	<0.005	DUP		VA05055093	0.91
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-287C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 980m

BEARING: 000 | DIP: -50°

DATE STARTED: 19-Jun-05 | DATE COMPLETED: 22-Jun-05

LOGGED BY: Terry Croteau
June 22-25, 2005

CONTRACTOR:
Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459608 NORTHING: 7099195
COORD SYSTEM: NAD 83: EASTING: 459490 NORTHING: 7099383
NAD 27 (CORRECTED for historic grid): EASTING: 459578 NORTHING: 7099205

SECTION LINE(historic grid): 459578

DRILLING DETAILS

Hole Diameter: HQ
Overburden:17.07m
Deviation:
Casing: 17.07m
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B292379-B292500
Requisition #: MASP448STRGOL.05Q Date Shipped: June 24, 2005
Lab Record #: VA05053953, VA05055092 Date Received: July 4 & 7, 2005
Sample Sequence: B381601-B381716
Requisition #: MASP448STRGOL.05Q Date Shipped: June 26, 2005
Lab Record #: VA05055279 Date Received: July 8, 2005

Duplicates:	B292382; B292402; B292422; B292442; B292462; B292482; B381602; B381622; B381642; B381662; B381682
Preparation Duplicate/ Check Assay:	B292389; B292409; B292429; B292449; B292469; B292489; B381609; B381629; B381649; B381669
Standards:	B292390 (1A); B292410 (3C); B292430 (5E); B292450 (6F); B292470 (7G); B292490 (2B); B381610 (7G); B381630 (3C); B381650 (4D); B381670 (3C)
Blanks:	B292396; B292416; B292436; B292456; B292476; B292496; B381616; B381636; B381656; B381676

FROM	TO	LITHOLOGY
17.07	219.46	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	339.0	50.2	005.0	006.0
150.0	340.0	48.6	006.0	007.0
219.5	342.0	47.6	008.0	009.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 1 of 10	
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-17.07m	0.00	17.07	Casing (no core recovery).						
10	17.07-219.46m	17.07	19.81	GND is broken w/ lim staining on frac, becoming pervasive @ 21.02m. Pieces are 10cm to gravel-sized, mixed w/ sugary texture. Recovery is poor.	2			1		
10		19.81	21.96	Core is more competent, recovery is good.	1			1		
10		21.96	22.86	Core is reddish colour and has dissem aspy. Contact w/ gouge @ 50° to CA @ 22.50m. Gouge is 7cm in width & contacts w/ limonized GND on other side.	1			1		
10		22.86	24.38	Core becomes more broken, pervasive lim & on frac sfc's. Trends to more clay alteration @ 24.00m.	2			2		
10		24.38	25.30	Core is softer; altered to clay. Sericite becomes dominant clay. Recovery good, still competent.	2	4				
10		25.30	27.43	Core is less competent & broken. Lim is pervasive and on frac. Pieces are gravel-sized, some show rounded faces.	2					
10		27.43	30.11	Core becomes more competent. Lim pervasive and on frac.	2					
10		30.11	31.52	Core is alt'd to clay, sugary texture. Dark red iron staining; possible qtz, py.	2	3		2		
10		31.52	32.00	Less ser alt'n, core is more competent. Good recovery, lim pervasive & frac.	2	2		1		
10		32.00	35.58	More intense ser alt'n, core is more fractured, recovery less. @ 33.47m: 5cm clay gouge @ 45° to CA.	2	3		2		
10		35.58	36.11	Core competent but fractured, lim on frac.	1	0		1		
10		36.11	36.74	Contact @ 45° w/ decomposed GND. Highly alt'd to clay w/ pervasive lim soft, but competent. Qtz eyes and GND frags present. Zone of hydrothermal alt'n.	4	3		3		
10		36.74	38.33	Return to competent GND. Lim on frac, minor pervasives. Vns crosscut frac angle. Vns @ 40°, frac @ 130°.	1			1		
10		38.33	39.62	Alt'd to sugary texture. Qtz eyes and GND frags present.	4	3		3		
10		39.62	47.02	GND becomes competent, less pervasive lim, mostly on fracs. Fracs predominantly @ 30° to CA, as are carb vnlets. 8cm clay gouge @ 44.60m @ 45° to CA, and 4cm clay gouge @ 44.75m @ 45° to CA.						
10		47.02	48.26	gravel size frags, lim pervasive and on frac.	2			2		
10		48.26	51.62	core more competent, recovery increases. fracs @ 40° and 145°. less pervasive lim, lim on fracs.	1			1		
10		51.62	51.82	GND soft w/ sugary texture, qtz eyes and GND frags present. relict qtz vn @ 51.82m. likely hydrothermal alt. lim pervasive.	3					
10		51.82	53.34	recovery decreases, core becomes fragmented, ser alteration increases on fracs. frags are gravel-sized to 15cm and angular.	3	2		1		
10		53.34	54.05	GND is competent, good recovery. pervasive lim & deep red stained. oxidized sulfide vns--red stain may be related to oxpy.	3			1		
10		54.05	60.96	core is more competent w/ less pervasive lim. fracs still show heavy lim stain, fracs have NO preferred orientation.	1					
10		60.96	61.14	moderately alt to chl, qtz vn is fractured and offset. aspy is oxidized heavily and has left vugs.	2	1		1		
10		61.14	67.06	core is becoming more competent, minor pervasive lim, mostly on fracs. few vns, fracs have no preferred orientation.	2	1		1		

DRILL LOG LEGEND P2

Selvages Ox. State
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages			% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																					B292379	17.07	18.29	0.087			VA05053953	1.22
																					B292380	18.29	19.81	0.051			VA05053953	1.52
																					B292381	19.81	21.34	0.013			VA05053953	1.53
																					B292382	19.81	21.34	0.017	DUP		VA05053953	1.53
																					B292383	21.34	21.96	0.007			VA05053953	0.62
																					B292384	21.96	22.86	0.031			VA05053953	0.9
																					B292385	22.86	24.38	0.022			VA05053953	1.52
																					B292386	24.38	25.30	0.150			VA05053953	0.92
																					B292387	25.30	26.60	0.055			VA05053953	1.3
																					B292388	26.60	28.02	0.070			VA05053953	1.42
																					B292389	26.60	28.02	0.090	PD/CA		VA05053953	1.42
																					B292390	STANDARD 1A		0.836	1A		VA05053953	
																					B292391	28.02	29.14	0.045			VA05053953	1.12
																					B292392	29.14	30.11	0.027			VA05053953	0.97
																					B292393	30.11	30.48	0.067			VA05053953	0.37
																					B292394	30.48	31.52	0.068			VA05053953	1.04
																					B292395	31.52	32.00	0.070			VA05053953	0.48
																					B292396	BLANK		<0.005			VA05053953	
																					B292397	32.00	33.53	0.034			VA05053953	1.53
1	1	1.0	1.0	45		0.0															B292398	33.53	35.05	0.084			VA05053953	1.52
	1	0.2	0.2	25		0.0						5.0									B292399	35.05	36.11	0.015			VA05053953	1.06
																					B292400	36.11	36.74	0.178			VA05053953	0.63
2	1	0.2	0.4	45		0.0						1.0									B292401	36.74	38.10	0.046			VA05053953	1.36
2	1	0.2	0.4	45		0.0						1.0									B292402	36.74	38.10	0.068	DUP		VA05053953	1.36
																					B292403	38.10	39.62	0.019			VA05053953	1.52
																					B292404	39.62	41.15	0.050			VA05053953	1.53
																					B292405	41.15	42.67	0.026			VA05053953	1.52
1	1	2.0	2.0	45		0.0															B292406	42.67	43.59	0.136			VA05053953	0.92
1	1	2.0	2.0	45		0.0															B292407	43.59	44.60	0.083			VA05053953	1.01
																					B292408	44.60	45.72	0.043			VA05053953	1.12
																					B292409	44.60	45.72	0.047	PD/CA		VA05053953	1.12
																					B292410	STANDARD 3C		0.084	3C		VA05053953	
1	1	0.2	0.2	45								1.0									B292411	45.72	47.02	0.067			VA05053953	1.3
																					B292412	47.02	48.26	0.046			VA05053953	1.24
1	1	0.2	0.2	45								2.0									B292413	48.26	49.22	0.063			VA05053953	0.96
1	4	0.2	0.2	45																	B292414	49.22	50.29	0.027			VA05053953	1.07
1	1	0.2	0.2	35		0.0															B292415	50.29	51.62	0.023			VA05053953	1.33
																					B292416	BLANK		<0.005			VA05053953	
1	1	0.2	0.2	35		0.0															B292417	51.62	52.14	0.040			VA05053953	0.52
1	4	0.5	0.5	35		0.0															B292418	52.14	53.34	0.051			VA05053953	1.2
1	1	0.2	0.2	70		0.0						1.0									B292419	53.34	54.05	0.069			VA05053953	0.71
1	6	2.0	3.0	70		0.0						100.0					90.0											
1	1	0.5	0.5	70		0.0															B292420	54.05	54.86	0.059			VA05053953	0.81
2	1	0.5	1.0	60		0.0															B292421	54.86	56.39	0.043			VA05053953	1.53
	1	0.5	1.0	60		0.0															B292422	54.86	56.39	0.036	DUP		VA05053953	1.53
2	1	1.0	1.5	55		0.0						5.0									B292423	56.39	57.91	0.036			VA05053953	1.52
																					B292424	57.91	59.44	0.047			VA05053953	1.53
1	1	0.2	0.2	65		0.0						5.0									B292425	59.44	60.96	0.039			VA05053953	1.52
1	1	3.0	3.0	?		0.0						1.0									B292426	60.96	61.14	0.098		unable to determine angle due to frac & offset.	VA05053953	0.18
																					B292427	61.14	62.48	0.065			VA05053953	1.34
																					B292428	62.48	64.01	0.121			VA05053953	1.53

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 3 of 10	
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		67.06	68.58	core even more competent, recovery very good. minor pervasive lim fracs @ 35° and 55°.	1					
10		68.58	74.68	GND is unalt. lim NO longer pervasive, limited to fracs. veinage increasing. GND is unalt, po occurs for first time in hole.	0					
10		74.68	75.01	less recovery, more alt. return of pervasive lim on interval, fracs have as preferred orientation. frac faces of core are reddish brown--likely due to oxpy. aspy present on faces.	2					
10		75.01	80.77	GND alt only as selvages. no pervasive lim, found on frac only. fracs normally at 50°, recovery is good.	0					
10		80.77	82.64	core is dark green in color and easily scratchable, heavily alt to chlorite. fracs are covered in red brown oxide, weathered py. minor dissem aspy. also found in sulphide vnlets. core is fractured and broken w/ reduced recovery.			4			
10		82.64	83.40	core is a very light white-green color. sericite dominant alt type. contact w/ chl section occurs at 65° @ 82.68m on an oxidized sulphide vn. core is fractured randomly, but is less broken. dissem py abundant.		3	2			
10		83.40	84.91	chl alt lessening, no sulphide vns are present.						
10		84.91	91.44	return to unalt GND. heavy lim staining on faces. fracs predominantly @ 50° to CA.	1					
10		91.44	96.84	unalt GND. trace lim stain on frac. ascent after 92.05m, recovery is very good. increase in number and frequency of vns.	0					
10		96.84	98.26	GND becomes crumbly, less competent. sericitic alt present on fracs.		2				
10		98.26	99.21	core becomes clay, green color, alt changes to chl. aspy present on some frac faces. slickensides present overprint aspy--post mineralization.			3			
10		99.21	99.62	unalt GND, good recovery.						
10		99.62	100.16	GND is bleached. mafics are absent. core is white-ser alt.		3				
10		100.16	101.39	core changes from white to green. becomes softer @ 100.98m. 7cm clay gouge unit at 50° to CA. cross cuts qtz vns. possible fault.		2	3			
10		101.39	106.68	unalt GND. frac at 45-50° to CA.						
10		106.68	107.10	GND is green-chl alt. qtz vns are fractured and crosscut by calcite vnlets.			3			
10		107.10	123.10	unalt GND, good recovery. fracs @ 45° and 60°. fracs are filled w/ carbonate from 111.25m-123.10m. vns appear to be dominated by po. selvages are mainly qtz, but chl may also be present. core shows an increase in veinage. @ 115.82m: rounded GND frags w/ pervasive lim -likely from drillers reaming.						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration, 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: 19-20-June-06

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B292429	62.48	64.01	0.082	PD/CA		VA05053953	1.53
																						B292430	STANDARD 5E		1.435	5E		VA05053953	
2	1	1.0	2.0	45		2.0	q/chl	4	0				1.0									B292431	64.01	65.53	0.054			VA05053953	1.52
2	1	1.0	1.5	45		0.0							1.0									B292432	65.53	67.06	0.160			VA05053953	1.53
5	1	1.5	5.5	45		0.0							5.0					70.0				B292433	67.06	68.58	0.103			VA05053953	1.52
5	1	1.5	4.5	50		0.0					10.0	1.0										B292434	68.58	70.10	0.546			VA05053953	1.52
4	1	1.0	3.0	50		0.0					20.0		5.0									B292435	70.10	71.63	0.065			VA05053953	1.53
																						B292436	BLANK		<0.005			VA05053953	
4	1	1.0	2.0	45		0.0					20.0	1.0										B292437	71.63	73.15	0.074			VA05053953	1.52
2	6	0.5	1.0	40									60.0					70.0				B292438	73.15	74.68	0.806			VA05053953	1.53
1	6	0.2	0.2	55		1.0	chl	3	0	10			60.0					90.0				B292439	74.68	75.01	0.129			VA05053953	0.33
1	1	0.2	0.2	55		0.0																B292440	75.01	76.20	0.058			VA05053953	1.19
5	1	0.2	1.0	55		3.0	qtz	3	0		10.0	0.1										B292441	76.20	77.72	0.035			VA05053953	1.52
5	1	0.2	1.0	55		3.0	qtz	3	0		10.0	0.1										B292442	76.20	77.72	0.123	DUP		VA05053953	1.52
4	1	1.0	3.0	55		0.0							3.0					80.0				B292443	77.72	79.25	0.129			VA05053953	1.53
5	1	1.0	2.6	70	55	2.0	qtz	3	0	3			5.0					40.0				B292444	79.25	80.77	0.162			VA05053953	1.52
4	1	0.5	2.0	60		2.0	chl	4	0		5.0	2.0	2.0					10.0				B292445	80.77	82.30	0.161			VA05053953	1.53
1	6	1.0	1.0	60		0.0				100								60.0				B292446	82.30	82.64	0.645			VA05053953	0.34
7	6	1.5	9.0	55		0.0				100								30.0				B292447	82.64	83.40	0.275			VA05053953	0.76
	1	0.5	0.5	45		6.0	chl	3	0	1	5.0		3.0									B292448	83.40	84.56	0.037			VA05053953	1.16
	1	0.5	0.5	45		6.0	chl	3	0	1	5.0		3.0									B292449	83.40	84.56	0.034	PD/CA		VA05053953	1.16
																						B292450	STANDARD 6F		2.860	6F		VA05053953	
2	1	1.0	1.2	45		0.0							2.0									B292451	84.56	85.34	0.242			VA05053953	0.78
3	1	1.0	1.4	45		1.0	q/chl	3	0		3.0		1.0									B292452	85.34	86.87	0.089			VA05053953	1.53
1	1	1.0	1.0	45		1.0	q/chl	3	0		4.0		2.0									B292453	86.87	88.39	0.083			VA05053953	1.52
3	1	2.0	3.5	45		0.5	qtz	2	0		2.0		0.1									B292454	88.39	89.92	0.061			VA05053953	1.53
2	1	1.0	1.5	40		1.0	qtz	2	0		25.0	2.0										B292455	89.92	91.44	0.058			VA05053953	1.52
																						B292456	BLANK		<0.005			VA05053953	
4	1	1.5	1.5	45		10	q/ser	3	0	26			5.0									B292457	91.44	92.17	0.416			VA05053953	0.73
3	1	1.0	2.5	30	20	0.0				5			2.0									B292458	92.17	92.96	0.145			VA05053953	0.79
4	1	1.5	4.0	45	30	15	q/ser			10			1.0									B292459	92.96	93.69	0.283			VA05053953	0.73
6	1	3.0	6.0	45		2.0	8	2	0		10.0											B292460	93.69	94.49	0.396			VA05053953	0.8
3	1	1.0	2.5	40							1.0	1.0	1.0									B292461	94.49	96.01	0.040			VA05053953	1.52
3	1	1.0	2.5	40							1.0	1.0	1.0									B292462	94.49	96.01	0.041	DUP		VA05053953	1.52
3	1	1.0	1.6	45		0.0					2.0											B292463	96.01	96.84	0.315			VA05053953	0.83
8	1	1.5	5.5	45	30	0.0					5.0		2.0									B292464	96.84	98.26	0.167			VA05053953	1.42
5	1	1.0	5.0	45		5.0	q/chl	4	0	10								70.0				B292465	98.26	99.21	0.313			VA05053953	0.95
1	1	2.0	2.0	50		10	chl	4	0		10.0											B292466	99.21	99.62	0.295			VA05053953	0.41
3	1	1.0	2.0	50		0.0					5.0											B292467	99.62	100.16	0.159			VA05053953	0.54
4	1	1.0	3.0	60	30	0.0					3.0											B292468	100.16	101.39	0.107			VA05053953	1.23
																						B292469	100.16	101.39	0.105	PD/CA		VA05053953	1.23
																						B292470	STANDARD 7G		4.410	7G		VA05053953	
																						B292471	101.39	102.11	0.046			VA05053953	0.72
7	1	1.0	4.5	60	30	0.0					30.0											B292472	102.11	103.63	0.159			VA05053953	1.52
9	1	2.0	6.2	30		1.0	qtz	4	0		10.0	0.1										B292473	103.63	105.16	0.311			VA05053953	1.53
7	1	1.0	5.5	30		1.0	qtz	4	0		5.0	0.1										B292474	105.16	106.68	0.182			VA05053953	1.52
3	1	2.0	6.0	30							1.0											B292475	106.68	107.10	0.091			VA05053953	0.42
																						B292476	BLANK		<0.005			VA05053953	
5	1	1.0	3.0	40		0.2	qtz	3	0		5.0		1.0									B292477	107.10	108.20	0.186			VA05053953	1.1
8	1	1.0	6.5	40	30	4.0	q/chl	3	0		15.0	1.0										B292478	108.20	109.73	0.736			VA05053953	1.53
																						B292479	109.73	111.25	0.301			VA05053953	1.52
9	1	2.0	7.0	40		0.2	qtz	3	0		10.0	1.0										B292480	111.25	112.78	0.197			VA05053953	1.53
6	1	1.0	5.0	40		1.0	qtz	3	0		5.0	1.0										B292481	112.78	114.30	0.455			VA05053953	1.52
6	1	1.0	5.0	40		1.0	qtz	3	0		5.0	1.0										B292482	112.78	114.30	0.255	DUP		VA05053953	1.52

DRILL HOLE # : DG05-287C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		123.10	126.31	GND is lighter in color, more feldspar, w/ min ser. core becomes marginally softer.		1				
10		126.31	129.54	core becomes softer as ser alt increases.		2				
10		129.54	132.59	core is more competent, ser alt is reduced to fracs only.						
10		132.59	133.76	unalt GND. greyish color, more competent, good recovery.						
		133.76	134.62	GND is dark green in color--chlorite alt. section also contains 3 massive sulphide vns up to 1cm thick @ 40° to CA.			3			
10		134.62	137.74	unalt GND w/ chl on frac faces. fracs @ 45° and 80°. po in vns, aspy in selvages, py on slickensides.						
10		137.74	138.68	core is light green. ser & chl alt. softer & less competent, contains sulphide vnlets; py.		2	2			
10		138.68	143.26	unalt GND, core is fractured and broken, chl is present on frac. the majority of frac angles are random, but 45° and 80° are still present.						
10		143.26	144.78	GND becomes softer, more ser alt present. @ 144.39m: 15cm clay gouge @ 45° to CA. slickensides present--fault.		2				
10		144.78	147.11	fault zone. core is highly alt'd to clays. qtz vns are powdery. GND frags present up to 5cm. the most intense deformation occurs from 146.20m-146.98m. core is black, very coherent clay containing winged (?) qtz eyes, showing a crustal rotation. fault contact @ 45° to CA. @ 146.44m: 5cm qtz frag containing ~15% py; py may have been emplaced during faulting. the py filled fracs appear to stem from the black clay, w/ a thin zone of py in the clay surrounding the qtz frag (~1mm).						
10		147.11	149.35	core is light green in color, soft but competent. fracs are irregular and random. the majority of vning is sulphide vnlets in fracs. py is dominant, but aspy also present.		2	3			
10		149.35	150.88	core is softer & broken and contains less chl and more ser. no sulphide vns, poor recovery.		3	1			
10		150.88	152.40	core regains coherency, more chl, less ser, sulphide vns return.						
10		152.40	153.92	core is again softer and broken, no sulphide vnlets, poor recovery.						
10		153.92	157.92	core regains coherence w/ increase in chl and decrease in ser. sulphide vns and vnlets return. recovery increases. chl/ser contact @ 45°, diss py present.						
10		157.92	159.30	core becomes unalt GND. more competent, good recovery. vns are mostly qtz. fracs @ 40° & 80°.						
10		159.30	162.57	GND alt by ser and chl. core is broken and fracs coated w/ ser. recovery is reduced to ~67%. sulphide vnlets dominant again, fracs are random.						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval				
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	iscordite	biotite	other		From	To		
6	1	0.5	3.0	40		1.0	qtz	3	0		10.0											B292483	114.30	115.82	0.276	
5	1	1.5	4.0	30		1.0	qtz	3	0		0.1											B292484	115.82	117.39	0.881	
2	1	1.0	1.2	30		0.0					5.0											B292485	117.39	118.87	0.187	
4	1	1.0	2.5	40		0.0					1.0											B292486	118.87	120.40	0.633	
4	1	2.0	5.0	30	40	1.0	chl	3	0		3.0	0.1					0.1					B292487	120.40	121.92	0.171	
3	1	0.2	0.6	30		0.0					10.0											B292488	121.92	123.10	0.220	
																						B292489	121.92	123.10	0.199	PD/CA
																						B292490	STANDARD 2B		3.450	2B
2	1	12	0.2	40		0.0					0.1		0.1									B292491	123.10	123.84	0.508	
3	1	0.2	0.2	40		0.0																B292492	123.84	124.97	0.643	
1	1	2.0	2.0	40		0.0					5.0		0.1									B292493	124.97	126.49	0.219	
4	1	3.0	2.5	40		0.0					2.0											B292494	126.49	128.02	0.042	
0																						B292495	128.02	129.54	1.875	
																						B292496	BLANK		<0.005	
2	1	1.0	2.0	40		0.0					2.0		0.1									B292497	129.54	131.06	0.328	
2	1	1.0	1.5	40		0.0					1.0											B292498	131.06	132.59	0.158	
2	1	1.5	2.0	45		0.0					2.0											B292499	132.59	133.76	1.380	
1	6	0.2	0.2	40		0.0				100																
3	6	0.2	0.6	45		0.0				100								0.0				B292500	133.76	134.62	0.550	
1	1	1.0	1.0	45		0.0				1																
2	1	1.5	2.0	40		0.0							1.0									B381601	134.62	135.64	1.015	
	1	1.5	2.0	40		0.0							1.0									B381602	134.62	135.64	0.180	DUP
	1	1.5	2.5	45	60	0.0				1												B381603	135.64	137.16	1.260	
2	1	1.0	1.5	45		0.0				1												B381604	137.16	137.74	0.729	
1	1	1.0	1.0	45		0.0				1			2.0									B381605	137.74	138.68	0.427	
1	6	0.5	0.5	45		0.0				100								60.0								
4	1	1.0	2.5	45		0.0				1			0.1									B381606	138.68	140.21	0.164	
3	1	1.0	2.0	50		1.0	chl	3	0		3.0		0.1									B381607	140.21	141.73	0.524	
2	1	1.0	2.0	45		0.0				5			1.0									B381608	141.73	143.26	0.533	
2	1	1.0	2.0	45		0.0				5			1.0									B381609	141.73	143.26	0.478	PD/CA
																						B381610	STANDARD 7G		4.620	7G
1	1	8.0	8.0	50		0.0					0.1	0.1	1.0					60.0				B381611	143.26	144.78	0.613	
0																						B381612	144.78	146.30	0.320	
1	1									15												B381613	146.30	147.11	2.240	
3	6	0.2	0.6	60		0.0				100								60.0				B381614	147.11	147.83	0.639	
2	6	0.2	0.4	60		0.0				100								40.0				B381615	147.83	149.35	0.445	
2	1	1.0	1.2	60		1.0	chl	4	0																	
																						B381616	BLANK		<0.005	
2										0.1												B381617	149.35	150.88	0.062	
4	6	0.2	0.8	60		0.0				100								70.0				B381618	150.88	152.40	0.434	
1	1	1.0	1.0	45		0.0				0.1																
1	1	1.0	1.0	45		0.0																B381619	152.40	153.92	0.298	
3	6	0.2	0.6	75		0.0				100								40.0				B381620	153.92	155.45	0.116	
3	1	1.5	2.5	45		0.0				15								20.0				B381621	155.45	156.97	0.354	
	1	1.5	2.5	45		0.0				15								20.0				B381622	155.45	156.97	0.226	DUP
	6	0.2	0.8	75		0.0				100								70.0				B381623	156.97	157.42	0.443	
6	1	1.0	3.5	70	85	6.0	q/chl	5	0				1.0									B381624	157.42	158.50	0.665	
1	6	0.2	0.2	60		0.0				100								20.0								
2	1	1.0	1.6	60		0.0							1.0									B381625	158.50	159.30	0.129	
2	1	0.2	0.4	70		0.0																B381626	159.30	160.02	0.680	
7	1	2.0	5.5	60		1.0	chl	4	0		5.0		1.0									B381627	160.02	161.54	0.516	
1	6	0.2	0.2	80		0.0				100																

Vein Comments?	CSV	Width
	VA05053953	1.52
	VA05053953	1.57
	VA05053953	1.48
	VA05053953	1.53
	VA05053953	1.52
	VA05053953	1.18
	VA05053953	1.18
	VA05053953	
	VA05053953	0.74
	VA05053953	1.13
	VA05053953	1.52
	VA05055092	1.53
	VA05055092	1.52
	VA05055092	
	VA05055092	1.52
	VA05055092	1.53
	VA05055092	1.17
	VA05055092	0.86
Jump in sample tag #'s is due to switching from old batch to new batch of sample books.	VA05055279	1.02
	VA05055279	1.02
	VA05055279	1.52
	VA05055279	0.58
	VA05055279	0.94
	VA05055279	1.53
	VA05055279	1.52
	VA05055279	1.53
	VA05055279	1.53
	VA05055279	
	VA05055279	1.52
qtz is in fault, not a vn but worth noting	VA05055279	0.81
	VA05055279	0.72
	VA05055279	1.52
	VA05055279	
core too broken for measurements.	VA05055279	1.53
	VA05055279	1.52
	VA05055279	1.52
	VA05055279	1.53
	VA05055279	1.52
	VA05055279	1.52
	VA05055279	0.45
	VA05055279	1.08
	VA05055279	0.8
	VA05055279	0.72
	VA05055279	1.52

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 7 of 10	
DRILL HOLE # : DG05-287C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		162.57	165.32	core is more intensely alt to clays. core is crumbly, soft and contains qtz eyes, and is coherent until disturbed.						
10		165.32	166.12	core becomes less alt, much more coherent, recovery is greatly increased. sulfide vnlets no longer present.						
10		166.12	174.04	unalt GND, core is grey-blue. recovery is excellent, vns are predominantly qtz.						
10		174.04	175.01	core is alt to ser and chl, light green color. @ 174.14m: 6cm grey qtz vn @ 50°, slickensides on end of vn.						
10		175.01	183.46	unalt GND, recovery excellent, fracs @ 30°.						
10		183.46	184.73	core is dark green in color, chl alt. contains massive sulphide vnlets--py. fracs @ 50°, as are the vns. core is fine grained.			2			
10		184.73	185.17	core appears more granular, alt is more intense, chl and ser present. soft but coherent core. massive sulphide vns present @ 184.73m & 185.17m, flanking the alt zone.		2	2			
10		185.17	186.63	GND becomes med-grained, still has green color--chl. fracs continue at 50°.			2			
10		186.63	187.45	less alt GND, starts fine-grained & changes gradually to med-gr.						
10		187.45	191.52	unalt med-gr GND, frac at high angle 75°.						
10		191.52	192.75	zone of chl alt. core is green and scratches easily. sulfide vnlets fill some fracs.			2			
10		192.75	213.84	unalt GND, fine-gr, frac @ 45° and 50°. vns follow fracs, dominant sulfide is po.						
10		213.84	216.96	unalt GND, med-gr. @ 213.86m: 0.2cm fault @ 65° to CA. py present overprinting slickensides. 15cm zone of chl alt around fault.						
10		216.96	219.46	fine-gr GND.						
				EOH						

DRILL LOG LEGEND P2

Selvages **Ox. State**
0 = No Alteration 0 = No Oxidized Sulphides
5 = Intense Alt'n 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	1.5	2.0	60		0.0				1												B381628	161.54	162.57	0.562			VA05055279	1.03
2	1	1.5	2.0	60		0.0				1												B381629	161.54	162.57	0.734	PD/CA		VA05055279	1.03
																						B381630	STANDARD 3C		0.093	3C		VA05055279	
3	6	0.4	0.6	40		0.0				90			10.0					60.0				B381631	162.57	164.02	1.260			VA05055279	1.45
3	1	1.0	2.2	40		0.0				3												B381632	164.02	165.32	1.625			VA05055279	1.3
2	1	0.5	0.7	40		0.0				0.1												B381633	165.32	166.12	0.242			VA05055279	0.8
6	1	1.0	4.5	45							5.0											B381634	166.12	167.64	0.674			VA05055279	1.52
1	4	0.5	0.5	30																									
7	1	3.0	5.0	50		0.0					5.0											B381635	167.64	169.16	0.394			VA05055279	1.52
																						B381636	BLANK		<0.005			VA05055279	
5	1	1.0	3.8	50		0.0				5	5.0		1.0									B381637	169.16	170.69	0.082			VA05055279	1.53
1	6	0.5	0.5	50		0.0				70			30.0					5.0				B381638	170.69	172.21	0.253			VA05055279	1.52
3	1	1.0	2.5	50		0.0					10.0																		
2	1	1.0	1.5	30		0.0							0.1									B381639	172.21	173.74	0.200			VA05055279	1.53
2	1	0.2	0.4	30							5.0											B381640	173.74	174.04	0.075			VA05055279	0.3
2	1	6.0	6.5	50		0.0				10												B381641	174.04	175.01	0.690			VA05055279	0.97
2	1	6.0	6.5	50		0.0				10												B381642	174.04	175.01	1.005	DUP		VA05055279	0.97
1	1	0.2	0.2	25		0.0				3	5.0											B381643	175.01	176.30	0.169			VA05055279	1.29
1	1	6.0	6.0	50		2.0	chl			10	3.0											B381644	176.30	177.43	0.747			VA05055279	1.13
2	1	1.0	1.0	50		0.0					1.0											B381645	177.43	178.93	0.574			VA05055279	1.5
1	1	3.0	3.0	50						2	7.0	1.0										B381646	178.93	179.86	11.850			VA05055279	0.93
3	1	0.2	0.6	40		0.0					1.0	0.1										B381647	179.86	181.36	0.236			VA05055279	1.5
	1	1.0	4.0	60		0.0					5.0											B381648	181.36	182.88	0.246			VA05055279	1.52
	1	1.0	4.0	60		0.0					5.0											B381649	181.36	182.88	0.342	PD/CA		VA05055279	1.52
																						B381650	STANDARD 4D		0.465	4D		VA05055279	
1	1	1.0	1.0	50						1	1.0											B381651	182.88	183.46	0.953			VA05055279	0.58
3	6	0.2	0.6	55		0.0				100								5.0				B381652	183.46	184.73	0.131			VA05055279	1.27
1	6	2.0	2.0	55		0.0				100												B381653	184.73	185.17	1.060			VA05055279	0.44
2	1	0.2	0.4	50		0.0																B381654	185.17	186.63	0.869			VA05055279	1.46
1	1	1.0	1.0	45		0.0				0.1												B381655	186.63	187.45	0.545			VA05055279	0.82
																						B381656	BLANK		<0.005			VA05055279	
2	1	0.2	0.4	50		0.0					5.0											B381657	187.45	188.98	0.324			VA05055279	1.53
2	1	0.2	0.4	50		0.0					2.0											B381658	188.98	190.50	0.654			VA05055279	1.52
4	1	1.0	1.6	60		1.0	chl	3	0		5.0	0.1	0.1									B381659	190.50	191.52	1.035			VA05055279	1.02
4	1	3.0	6.0	60		0.0							20.0									B381660	191.52	192.72	4.550			VA05055279	1.2
1	1	0.2	0.2	50		0.2	qtz				0.1											B381661	192.72	193.55	0.789			VA05055279	0.83
1	1	0.2	0.2	50		0.2	qtz				0.1											B381662	192.72	193.55	1.765	DUP		VA05055279	0.83
2	1	1.0	1.0	30		0.0																B381663	193.55	195.07	0.855			VA05055279	1.52
7	1	1.0	5.0	60	30	0.0					3.0											B381664	195.07	196.60	0.654			VA05055279	1.53
3	1	1.0	2.0	53		1.0	qtz	3	0		10.0	2.0						10.0				B381665	196.60	198.12	0.503			VA05055279	1.52
3	1	2.0	0.6	50		0.0																B381666	198.12	199.64	0.193			VA05055279	1.52
5	1	0.2	1.0	65	40	0.2	qtz	3	0													B381667	199.64	201.17	0.570			VA05055279	1.53
3	1	0.2	0.6	60		0.2	qtz	3	0		3.0											B381668	201.17	202.69	0.158			VA05055279	1.52
3	1	0.2	0.6	60		0.2	qtz	3	0		3.0											B381669	201.17	202.69	0.206	PD/CA		VA05055279	1.52
																						B381670	STANDARD 3C		0.090	3C		VA05055279	
3	1	1.0	3.0	40		0.2	qtz	3	0		0.1											B381671	202.69	204.22	0.312			VA05055279	1.53
4	1	0.5	2.0	70		0.0							1.0									B381672	204.22	205.74	1.020			VA05055279	1.52
3	1	1.0	1.7	60		0.2	qtz	3	0		3.0											B381673	205.74	207.26	1.605			VA05055279	1.52
5	1	1.0	2.7	60							5.0		10.0									B381674	207.26	208.79	4.360			VA05055279	1.53
6	1	1.0	3.5	65		0.0					5.0	1.0										B381675	208.79	210.31	0.388			VA05055279	1.52
																						B381676	BLANK		<0.005			VA05055279	
	1	2.0	3.0	55		4.0	q/chl	3	0		1.0											B381677	210.31	211.84	1.395			VA05055279	1.53
1	1	2.8	2.5	50		0.0				5												B381678	211.84	213.36	3.810			VA05055279	1.52
1	4	0.2	0.2	25																									
2	1	0.2	0.4	65		0.0				5												B381679	213.36	214.88	0.353			VA05055279	1.52
2	1	0.2	0.4	65		0.0					10.0											B381680	214.88	216.41	1.710			VA05055279	1.53
3	1	0.2	0.6	65							5.0											B381681	216.41	217.93	1.590			VA05055279	1.52
3	1	0.2	0.6	65							5.0											B381682	216.41	217.93	1.225	DUP		VA05055279	1.52

DRILL LOG LEGEND P1	DATE: 19-20-June-05	PAGE 9 of 10	
DRILL HOLE # : DG05-287C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n
Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: 19-20-June-05

LOGGED BY: Terry Croteau & Tom Patchell

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS									% of VEIN & DISSEMINATED MATERIAL																		
						Selvages				Sulphides								Oxidation						Interval				
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
3	1	0.2	0.6	65							5.0											B381683	217.93	219.46	1.060			VA05055279	1.53
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-288C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 905m

BEARING: 000 | DIP: -50°

DATE STARTED: 20-Jun-05 | DATE COMPLETED: 22-Jun-05

LOGGED BY: Terry Croteau July 1-5, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459109 NORTHING: 7099040

COORD SYSTEM: NAD 83: EASTING: 458991 NORTHING: 7099224

NAD 27 (CORRECTED for historic grid): EASTING: 459079 NORTHING: 7099050

SECTION LINE(historic grid): 459079

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 10.36m

Deviation:

Casing: 10.36m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary. EOH corrected by DH (Nov).

FROM	TO	LITHOLOGY
10.36	195.37	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B380453-B380610

Requisition #: MASP448STRGOL.05Q Date Shipped: July 8, 2005

Lab Record #: VA05060563 Date Received: 21-July-2005

Sample Sequence: B381717-B381878

Requisition #: MASP448STRGOL.05Q Date Shipped: July 8, 2005

Lab Record #: VA05058631 Date Received: 15-July-2005

Special Note: Samples divided between lab records - entire hole between these two.

Duplicates:	380462, 380482, 380502, 380522, 380542, 380562, 380582, 380602
Preparation Duplicate/ Check Assay:	380449, 380469, 380489, 380509, 380529, 380549, 380569, 380589, 380609
Standards:	380450 (3C), 380470 (2B), 380490 (7G), 380510 (5E), 380530 (3C), 380550 (3C), 380570 (4D), 380590 (4D), 380610 (2B)
Blanks:	380456, 380476, 380496, 380516, 380536, 380556, 380576, 380596

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.0	350.5	-51.0	016.5	017.5
120.0	359.1	-52.0	025.1	026.1
195.0	356.0	-56.6	022.0	023.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 1 of 8		
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 10.36			Casing; recovered 30cm of GND. Pervasive lim, half of the core is altered to clay, oxidized aspy vein present	3					
10	10.36 - 195.37			GND - See previous logs for description						
10		10.36	12.19	Core is soft but coherent. Light grey in color. Oxidized sulphide veins are present throughout. Aspy is dominant sulphide. No lim present				3		
10		12.19	13.72	Core is still soft, but becomes broken into gravel sized pieces. Minor lim on frac. Recovery is poor.	1			3		
10		13.72	15.24	Core becomes more solid, clay alt'n present on fractures. Fractures show no preferred orientation. No lim present	1			2		
10		15.24	18.29	GND is light grey in color and highly fractured. Fractures normally @ 45° and 120°. Clay alteration on fractures is greatly reduced. No visible veins present.	1			1		
10		18.29	21.63	First occurrence of pervasive lim. Fractures are at 30° and 70°. Sulphide veins present are generally found at 30° to CA. The number and size of the sulphide veins have increased. Core is still broken, but most (85%) of the pieces are greater than 10cm. Recovery still poor.	3					
10		21.63	29.32	GND - lim is pervasive and heavily stains fractures. Clay alt'n is also common on fracture faces. Core is fractured and broken with 30% gravel size, 50% up to 10 cm and 20% greater than 10 cm. Fractures occur at 50° and 130° to CA. Sulphide veins continue to be present. @22.06m - 2cm sulphide vein at 30° to CA. Contact with quartz vein. Aspy dominant sulphide.	3			1		
10		29.32	30.48	Core is much more competent, good recovery. Less pervasive lim, and a decrease in sulphide veins.	2					
10		30.48	32.00	Core becomes fragmented into gravel sized pieces (80%) and pieces up to 10cm (20%). Pervasive lim is almost absent, but fractures are coated.	1					
10		32.00	34.13	GND is soft but coherent. Clay alt'n present, core has sugary texture. Pervasive lim increased as well as that on frac faces. Fractures at 20° and 100°.	3			2		
10		34.13	34.43	End of pervasive limonite						
		34.43	36.58	GND has become silicified. Blue-grey color. Disseminated aspy, and py found throughout. There is no visible contact with unalt'd core at beginning of interval. Contact at end, 70° to CA.						
10		36.58	41.15	Unaltered GND. Dark grey color, fractures at 60° and 110°. Euhedral aspy crystals found on frac faces. Veins run parallel to fractures. Core is broken in places with 20% of pieces <10cm.						
10		41.15	45.72	GND is silicified. Grey green color. Highly fractured and broken. Euhedral aspy crystals growing on faces. Most pieces (85%) are gravel sized, very angular.			2			Si
10		45.72	50.89	Unaltered GND. Dark Grey color, more competent and increased recovery. Small qtz veins present (most <.5 cm) as sheeted vein system. Aspy can still be found on most frac faces. @48.62m - 10cm clay altered section. Contact at 50° to CA			1			
10		50.89	51.82	Clay alt'd GND is granular with abundant euhedral aspy crystals.				2		
10		51.82	52.72	Unaltered GND. Fractured and broken (80% > 5 cm)						
10		52.72	54.86	GND is bleached, mafics almost completely absent. Aspy is present as fracture fill, in veins, and as diss euhedral crystals. Core is broken 60% < 10 cm. Fractures at 40° and 60°. Color likely due to veining.		3				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration, 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	6	0.2	0.4	40		0.0							100.0					70.0				B380443	10.06	10.67	0.057			VA05060563	0.61
6	6	0.2	1.2	50		0.0							100.0					70.0				B380444	10.67	12.19	0.377			VA05060563	1.52
0																						B380445	12.19	13.72	0.029			VA05060563	1.53
1	6	0.2	0.2	50		0.0							100.0					70.0				B380446	13.72	15.24	0.028			VA05060563	1.52
0																						B380447	15.24	16.76	0.078			VA05060563	1.52
																						B380448	16.76	18.29	0.317			VA05060563	1.53
0																						B380449	16.76	18.29	0.322	PD/CA		VA05060563	1.53
																						B380450	STANDARD 3C		0.100	3C		VA05060563	
5	6	0.2	0.2	50		0.0							100.0					70.0				B380451	18.29	19.81	0.230			VA05060563	1.52
2	6	1.5	1.7	50		0.0							100.0					10.0				B380452	19.81	21.34	0.354			VA05060563	1.53
2	6	0.2	0.4	40		0.0																B380453	21.34	22.02	0.128			VA05060563	0.68
2	6	2.0	3.0	30		0.0							100.0					10.0				B380454	22.02	22.10	1.815			VA05060563	0.08
1	6	0.2	0.2	40		0.0							100.0					10.0				B380455	22.10	22.86	0.059			VA05060563	0.76
																						B380456	BLANK		<0.005			VA05060563	
2	6	0.2	0.4	40		0.0							100.0					25.0				B380457	22.86	24.38	0.069			VA05060563	1.52
1	6	0.2	0.2	40		0.0							100.0					10.0				B380458	24.38	25.91	0.076			VA05060563	1.53
1	1	1.5	1.5	40		0.2	q	3	0				15.0									B380459	25.91	27.43	0.047			VA05060563	1.52
2	1	0.5	0.7	40		0.2	q	3	0				40.0									B380460	27.43	28.86	0.083			VA05060563	1.43
2	6	0.2	0.4	40		0.0							100.0					10.0				B380461	28.86	30.48	0.098			VA05060563	1.62
2	6	0.2	0.4	40		0.0							100.0									B380462	28.86	30.48	0.080	DUP		VA05060563	1.62
2	6	0.2	0.4	40		0.0							100.0					25.0				B380463	30.48	32.00	0.136			VA05060563	1.52
3	1	0.2	0.6	30		0.2	q	3	0				10.0									B380464	32.00	33.53	0.073			VA05060563	1.53
0																						B380465	33.53	34.43	0.072			VA05060563	0.90
2	6	0.2	0.4	40									100.0									B380466	34.43	35.05	0.127			VA05060563	0.62
2	6	0.2	0.4	40									100.0									B380467	35.05	36.58	0.057			VA05058631	1.53
1	1	4.0	4.0	30		0.0							50.0									B380468	36.58	38.10	0.382			VA05058631	1.52
1	1	4.0	4.0	30		0.0							50.0									B380469	36.58	38.10	0.354	PD/CA		VA05058631	1.52
																						B380470	STANDARD 2B		3.390	2B		VA05058631	
2	1	0.2	0.4	60		0.0							15.0									B380471	38.10	39.60	0.082			VA05058631	1.50
11	1	0.2	2.2	60		0.2	q	3	0				10.0					25.0				B380472	39.60	41.15	0.070			VA05058631	1.55
3	6												100.0									B380473	41.15	42.67	0.053		Vein broken into pieces	VA05060563	1.52
4	1	0.5											10.0									B380474	42.67	44.20	0.124		Vein broken into pieces	VA05060563	1.53
2	6	0.2											100.0									B380475	44.20	45.72	0.132		Vein broken into pieces	VA05060563	1.52
																						B380476	BLANK		<0.005			VA05060563	
7	1	0.2	1.4	60	120	0.2	q	3	0				20.0									B380477	45.72	47.24	0.171			VA05060563	1.52
6	1	0.2	1.2	60		0.2	q	3	0				10.0									B380478	47.24	48.77	0.143			VA05058631	1.53
4	1	0.2	0.8	60		0.2	q	3	0				10.0									B380479	48.77	50.29	0.102			VA05058631	1.52
2	1	0.5	0.7	60		0.2	q	3	0				5.0									B380480	50.29	51.82	0.133			VA05058631	1.53
3	1	0.5	1.2	30		0.2	q	3	0				5.0									B380481	51.82	52.72	0.466			VA05058631	0.90
3	1	0.5	1.2	30		0.2	q	3	0				5.0									B380482	51.82	52.72	0.543	DUP		VA05058631	0.90
6	6	0.2	1.2	40									100.0					25.0				B380483	52.72	53.34	0.740			VA05058631	0.62
10	6	0.2	2.0	40									100.0					25.0				B380484	53.34	54.86	0.737			VA05058631	1.52

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 3 of 8		
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		54.86	56.00	GND is less bleached, bt becomes visible. Core still contains significant aspy veinlets and grey qtz veins with above avg concentrations. @55.22m core is broken into gravel sized pieces with aspy on fractures.		1				
10		56.00	59.44	GND in larger pieces, dark grey in color. Carbonate on frac surfaces, and aspy veinlets fewer in number. Euhedral aspy crystals still present on many frac faces.				1	1	
10		59.44	60.98	GND is soft, and altered to clay - sugary texture. Core breaks when handled. Recovery is poor. Diss aspy present.		1		2		
10		60.98	65.53	GND more coherent, less clay alt'n - found only on fracture. High aspy concentration in veins. Fractures @ 10°, 40° and 160°. Recovery is good.				1		
10		65.53	68.58	Core is broken and 80% is gravel sized or smaller, 20% > 5cm. Clay alteration has left much of the core with a sugary texture. Diss aspy present. Recovery is poor.				3		
10		68.58	70.10	Very poor recovery. Intense clay alteration. Core is broken into gravel sized pieces (20%) and smaller (80%). Sugary texture, looks like broken concrete. Aspy with slickensides found on several faces.				4		
10		70.10	71.63	Clay alteration is less intense. Recovery increased. Core is still broken into gravel sized (40%) and larger (50%). Diss aspy can be found within fractures at 50° and 110°.				2		
10		71.63	76.20	Good recovery. Competence is greatly increased. Fractures at 30°, 50° and 140°. Carbonate fills many fractures and is found on frac faces. Aspy and chl also found on frac surfaces.			1	1	1	
10		76.20	77.72	Core is broken into gravel sized (85%) and larger pieces. Diss aspy present. Chl on frac as well as carb. Sulphide veins are oxidized.			1		1	
10		77.72	79.25	Core is still broken, but pieces are larger. Some faces contain aspy with slickensides. Carb and chl still on faces			1		1	
10		79.25	82.30	Core is light green in color and shows increased veining. Carb veins present and selvages on qtz are cb. Frac at 60° and 105°.			2		1	
10		82.30	90.37	Core is dark grey, less carb alt'n present. Chl still present on frac. Veins are still small (< 0.2 cm) with above avg aspy percentages. @85.04m, aspy on face showing slickensides. @85.14m, 6cm gouge. Qtz eyes and GND frags present. No visible contact; @85.24m, 7cm gouge @ 40° to CA. Qtz eyes and GND frags present.			2		1	
10		90.37	94.49	Core is light green color with diss aspy found throughout. Sulphide veinlets are common. Carb alt'n in core, but more present on frac faces. Fractures at 60° and 140°.		1	3		2	
10		94.49	98.31	Core is grey, less chl alt. Carb alt is still present on frac. There is a reduction in the number of veins and sulphides present. @97.01 7 cm bleached section with diss aspy -> likely selvage, but no vein visible		1	1		1	
10		98.31	99.06	Core is green (<10% mafics), fractures filled with aspy. Selvages also contain aspy. Increase in sulphide veins.			3			

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	6	0.2	1.0	40		0.0							100.0									B380485	54.86	56.00	0.697			VA05058631	1.14
5	6	0.2	1.0	40		0.0							100.0									B380486	56.00	56.37	0.096			VA05058631	0.37
2	6	0.2	0.4	40		0.0							100.0									B380487	56.37	57.71	0.148			VA05060563	1.34
4	1	1.0	1.6	50		0.2	q	3	0				15.0									B380488	57.71	59.44	0.178			VA05060563	1.73
4	1	1.0	1.6	50		0.2	q	3	0				15.0									B380489	57.71	59.44	0.172	PD/CA		VA05060563	1.73
																						B380490	STANDARD 7G		4.550	7G		VA05060563	
4	6	0.2											100.0									B380491	59.44	60.98	0.108		Vein broken into pieces	VA05060563	1.54
3	1	1.0	2.5	40		0.5	q	3	0				15.0									B380492	60.98	62.48	0.172			VA05058631	1.50
3	6	0.2	0.6	40									100.0									B380493	62.48	64.01	0.068			VA05058631	1.53
3	1	0.5	0.9	50		0.2	q	4	0				20.0									B380494	64.01	65.53	0.156			VA05058631	1.52
1	6																					B380495	65.53	67.06	0.091		Interval intensel altered to clay	VA05058631	1.53
																						B380496	BLANK		<0.005			VA05058631	
2	1	0.2	0.4	50		0.2	q	3	0				5.0									B380497	67.06	68.58	0.143			VA05058631	1.52
3	1	0.2	0.6										10.0									B380498	68.58	70.10	0.122		Vein broken into pieces	VA05058631	1.52
3	6	0.2	0.6	50									10.0									B380499	70.10	71.63	0.130		Vein broken into pieces	VA05058631	1.53
6	1	1.0	2.4	50		0.2	q	4	0				5.0									B380500	71.63	73.15	0.224			VA05058631	1.52
3	1	0.5	0.9	50	160	2.0	q	3	0				10.0									B380501	73.15	74.68	0.280		Most aspy found in sievages	VA05060563	1.53
3	1	0.5	0.9	50	160	2.0	q	3	0				10.0									B380502	73.15	74.68	0.278	DUP		VA05060563	1.53
6	1	0.2	1.2	50		0.5	q	3	0				5.0									B380503	74.68	76.20	0.377			VA05060563	1.52
1	6	0.2	0.2	50									100.0																
2	1	0.5	0.7	50		0.2	chl	4	0				5.0									B380504	76.20	77.72	0.361			VA05060563	1.52
3	1	0.5	0.9	50		3	q	4	0				5.0									B380505	77.72	79.25	0.216		Aspy in selvages	VA05060563	1.53
10	1	0.5	1.7	50		0.2	cb	4	0				10.0									B380506	79.25	80.77	0.206		Aspy in selvages and veins	VA05060563	1.52
4	1	0.2	1.1	50		1.0	cb	4	0				5.0									B380507	80.77	82.30	0.114			VA05060563	1.53
2	4	0.5	1.0	30		0.0																					Diss aspy found near cb vein		
2	1	0.2	0.4	60		0.2	q	4	0				1.0									B380508	82.30	83.82	0.133			VA05060563	1.52
2	1	0.2	0.4	60		0.2	q	4	0				1.0									B380509	82.30	83.82	0.140	PD/CA		VA05060563	1.52
																						B380510	STANDARD 5E		1.470	5E		VA05060563	
4	1	0.2	0.8	60		0.2	q	3	0				5.0									B380511	83.82	85.34	0.248			VA05060563	1.52
3	1	0.2	6.0	60		0.2	q	3	0				1.0									B380512	85.34	86.51	0.089			VA05060563	1.17
1	1	0.2	0.2	60		0.2	q	3	0				1.0									B380513	86.51	88.39	0.201		Veins broken, aspy in selvage	VA05060563	1.88
1	1	0.5	0.5	50		0.2	cb	3	0				1.0									B380514	88.39	89.92	0.302			VA05060563	1.53
1	1	0.2	0.2	50		0.2	q	4	0				1.0									B380515	89.92	90.37	0.239			VA05060563	0.45
																						B380516	BLANK		<0.005			VA05060563	
4	1	1.0	1.4	50		0.5	cb	4	0				10.0									B380517	90.37	91.44	0.328			VA05060563	1.07
2	1	0.2	0.4	50		1.0	q	3	0				3.0									B380518	91.44	92.96	0.330		Aspy in selvages	VA05060563	1.52
5	1	0.2	1.7	50							0.1		3.0									B380519	92.96	94.49	0.488			VA05060563	1.53
4	1	0.2	0.8	50	140	0.2	q	2	0				0.1									B380520	94.49	96.01	0.316			VA05060563	1.52
4	1	0.2	0.8	50		2.0	q	4	0				5.0									B380521	96.01	97.54	0.562		Aspy in selvage and vein	VA05060563	1.53
4	1	0.2	0.8	50		2.0	q	4	0				5.0									B380522	96.01	97.54	0.437	DUP		VA05060563	1.53
4	1	0.2	0.8	50		0.2	q	2	0				1.0									B380523	97.54	98.31	0.577			VA05060563	0.77
4	6	1.0	1.6	50									100.0									B380524	98.31	99.06	0.325			VA05060563	0.75
2	1	0.5	0.7	50		0.5	q	4	0				0.1																

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 5 of 8			
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered		Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		99.06	108.60	GND is light grey color with fractures at 50° and 140°. Fracture faces are covered with carb and ser. Numerous aspy veinlets present, but a decline in qtz veins. Aspy with slickensides present on some fractures (5%) others (50%) have euhedral aspy crystals.						
10		108.60	109.73	Core is light green color and contains diss aspy. Fractures show ser and carb alt'n and are at 40° and 120°. Diss py present. @109.23m, 3cm heavily altered to clay at 40° to CA. Slickensides present.		1	2		1	
10		109.73	112.78	Core becomes broken, with more clay alteration on broken surfaces. Chl alt'n is reduced. Aspy with slickensides found on some frac surfaces.		1	1		2	
10		112.78	113.40	Core is light green color with ser and carb on frac surfaces. Diss aspy present as well as an increase in the number of veins and % sulphides.		1	2		1	
10		113.40	118.34	Return to dark grey GND. Rock is fractured and broken. Fractures show euhedral aspy crystals, 5% have aspy with slickensides. Carb alt'n still occurs on most (80%) frac faces. Veins continue to be small and are found in sheeted sets.					1	
10		118.34	119.12	Intense clay alteration follows low angle fractures (relative to CA) 0-20° and 160-180°. Core is soft and contains diss aspy.		3	1	2	2	
10		119.12	123.44	GND is light grey in color and chl alt'n is common on frac faces. Carb veins and veinlets become more numerous, cross cutting qtz and sulphide veins at 140° and 170°.		1	2	1	1	
10		123.44	129.54	Alteration is reduced, minor chl and ser on frac surfaces. Sheeted vein sets are present. Veins are small (0.2 cm) and most contain aspy.		1	1		1	
10		129.54	131.06	Core is green, increased chl alt'n. Rock is soft but competent. Veins are larger in this section and sulphide content is higher.			2		1	
10		131.06	134.11	Core returns to dark grey color. Sheeted vein sets more frequent @ 45°. Carb veinlets crosscut at 175°.					1	
10		134.11	141.73	The end of the sheeted veins. Carb filled fractures are common. Fractures are at 30° and 145° to CA. GND is dark grey in color. Recovery is good. @140.11m, clayey gouge; qtz eyes and GND frags present.					2	
10		141.73	143.26	GND is greenish color with less carb alt and veins. Ser and chl on frac surfaces. Fractures at 60° and 165°.		1	2	1		
10		143.26	149.35	Unaltered GND. Dark grey color. Most (95%) of veins are carb veins. Fractures also filled with carb running at 20°, 40°, 70° and 170°. Slickensides on frac surface with minor aspy showing same feature.						

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides									Oxidation					Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6	60		0.2	q	3	0				5.0									B380525	99.06	100.58	0.303			VA05060563	1.52
4	6	0.2	0.8	60									100.0									B380526	100.58	102.11	0.174			VA05058631	1.53
4	1	0.2	8.0	60		0.2	q	3	0				5.0									B380527	102.11	103.63	0.131			VA05058631	1.52
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380528	103.63	105.16	0.157			VA05058631	1.53
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380529	103.63	105.16	0.155	PD/CA		VA05058631	1.53
																						B380530	STANDARD 3C		0.106	3C		VA05058631	
1	1	0.2	0.2	60		0.2	q	3	0				3.0									B380531	105.16	106.68	0.197			VA05060563	1.52
7	6	0.2	1.4	60									100.0																
3	1	0.2	0.6	60		0.2	q	3	0				0.1									B380532	106.68	108.20	0.155			VA05060563	1.52
1	1	0.2	0.2	60		0.2	q	3	0													B380533	108.20	108.60	0.089			VA05060563	0.40
3	1	0.2	0.6	60		0.2	chl	3	0				5.0									B380534	108.60	109.73	0.184			VA05060563	1.13
																						B380535	109.73	111.25	0.244			VA05060563	1.52
3	1	0.2	0.6	60		0.2	q	4	0				1.0									B380536	BLANK		<0.005			VA05060563	
1	1	0.5	0.5	40									0.1									B380537	111.25	112.78	0.186		Veins at 60 deg have higher sulfide content	VA05060563	1.53
6	1	1.0	3.7	60	40	0.2	chl	3	0				10.0									B380538	112.78	113.40	0.261			VA05060563	0.62
2	1	0.5	0.7	60		0.2	q	4	0				1.0									B380539	113.40	114.30	0.181			VA05060563	0.90
4	1	0.2	0.8	60		0.2	q	4	0				0.1									B380540	114.30	115.82	0.123			VA05058631	1.52
4	1	0.5	1.1	60		0.2	q	4	0				3.0									B380541	115.82	117.35	0.130			VA05058631	1.53
4	1	0.5	1.1	60		0.2	q	4	0				3.0									B380542	115.82	117.35	0.150	DUP		VA05058631	1.53
9	1	0.2	1.8	50	170	0.2	q	4	0				5.0									B380543	117.35	118.34	0.133			VA05058631	0.99
2	1	0.2	0.4	50		0.5	q	4	0				3.0									B380544	118.34	119.12	0.173			VA05060563	0.78
2	6	0.2	0.4	40									100.0					25.0				B380545	119.12	120.40	0.191			VA05060563	1.28
1	4	0.5	0.5	20																									
1	1	0.2	0.2	40	30	0.2	q	2	0				3.0									B380546	120.40	121.92	0.138			VA05060563	1.52
7	1	0.2	1.4	45		0.2	q	2	0				3.0									B380547	121.92	123.44	0.303			VA05060563	1.52
6	1	0.2	1.2	45		0.1	q	2	0				5.0									B380548	123.44	124.97	0.188			VA05060563	1.53
6	1	0.2	1.2	45		0.1	q	2	0				5.0									B380549	123.44	124.97	0.199	PD/CA		VA05060563	1.53
																						B380550	STANDARD 3C		0.098	3C		VA05060563	
2	1	0.5	0.7	45		0.2	q	3	0				5.0									B380551	124.97	126.49	0.067			VA05060563	1.52
6	1	0.2	0.2	45		0.2	q	4	0				3.0									B380552	126.49	128.52	0.142			VA05060563	2.03
4	1	0.2	0.8	45		0.2	q	3	0				3.0									B380553	128.52	129.54	0.123			VA05058631	1.02
8	1	2.0	2.8	45		0.2	q	2	0				5.0					25.0				B380554	129.54	131.06	0.178			VA05058631	1.52
21	1	0.2	4.2	40		0.2	q	4	0				1.0									B380555	131.06	132.59	0.124			VA05058631	1.53
																						B380556	BLANK		0.009			VA05058631	
21	1	0.2	4.2	40		0.2	q	4	0				1.0									B380557	132.59	134.11	0.169			VA05058631	1.52
8	1	0.2	1.6	40									0.1									B380558	134.11	135.64	0.157			VA05058631	1.53
7	1	0.2	1.4	40		0.2	q	2	0				1.0									B380559	135.64	137.16	0.091			VA05058631	1.52
7	1	0.2	1.4	40		0.2	q	3	0				0.1									B380560	137.16	138.68	0.046			VA05060563	1.52
2	1	0.2	0.4	40		0.2	q	4	0				0.1									B380561	138.68	140.21	0.056			VA05060563	1.53
2	1	0.2	0.4	40		0.2	q	4	0				0.1									B380562	138.68	140.21	0.072	DUP		VA05060563	1.53
7	1	0.2	1.4	40		0.2	q	3	0				1.0									B380563	140.21	141.73	0.105			VA05060563	1.52
2	1	0.2	0.4	40									0.1									B380564	141.73	143.26	0.029			VA05060563	1.53
5	4	0.5	1.1	30																		B380565	143.26	144.78	0.035			VA05060563	1.52
3	4	0.2	0.6	30																		B380566	144.78	146.30	0.027			VA05060563	1.52
4	4	0.2	0.8	30	170																	B380567	146.30	147.83	0.017			VA05060563	1.53
4	1	0.2	0.8	30		0.2	q	2	0				0.1									B380568	147.83	149.35	0.028			VA05060563	1.52
4	1	0.2	0.8	30		0.2	q	2	0				0.1									B380569	147.83	149.35	0.029	PD/CA		VA05060563	1.52

DRILL LOG LEGEND P1	DATE: June 20 - 22, 2005 PAGE 7 of 8		
DRILL HOLE # : DG05-288C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescen 5 = Strong Efferves

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		149.35	151.49	Reduction in carb veins, return to qtz veins. Chl alt'n dominant. Fractures occur at 40° and 95°.		1	2		1	
10		151.49	153.92	Rock is light grey green color, and shows clay alt'n. Qtz eyes and GND pieces are present indicating hydrothermal alt'n. Core is highly fractured and broken into gravel sized pieces (45%) and >5cm (55%). Gouge contacts @ 30° to CA @ 152.40m,for 8cm.		1	1	2		
10		153.92	157.74	Core is green and peach coloured. Selvages and fractures are filled with K-spar and carbonate. Py makes its first appearance as a sulphide vein @ 154.72m. Frac at 40° and 110° @157.11m, 10cm gouge @ 60° to CA, followed by diss aspy in 8cm of intense chl alt'n.			2		2	3
10		157.74	161.54	Dark grey GND with minor ser, carb and chl alt'n on fracture faces. Fractures at 30°, 70°, and 170°. Veins crosscut by 170° fractures. Euhedral aspy crystals present on frac faces @160.02m to 161.54m.		1	1	1		
10		161.54	166.12	Core is green with peach-filled fracs and selvages. K-spar grains are peach in color, combined with chl to give distinct color. Diss aspy present from 161.54 - 164.02m. Diss py present 164.02 - 164.50m.			2		2	3
10		166.12	172.21	Dark grey GND, chl and carb on frac faces. Diss aspy from 167.64 - 169.16m. Very few veins. Those present are small (0.2cm or less). Po makes its first major appearance @ 171.30m.			1		1	
10		172.21	173.48	Intense clay alt'n has made core soft and brittle. Fragments of unaltered GND can be seen within. Fractures filled with carb. Contact with unaltered GND at 30° to CA. Diss aspy is present.				3	1	
10		173.48	179.83	Light grey, med gr GND. Fractures contain ser and carb alt'n. Fractures @ 20° and 50°. Very few veins found in this section. Those that do occur are 0.2cm or less.		1			2	
10		179.83	182.88	GND is finer grained with less carb alt'n. Fracture surfaces show chl alt'n and euhedral aspy crystals. Core is highly fractured and broken. 40% gravel size, 60% > 5cm.			2			
10		182.88	195.37	Fine gr unaltered GND. Dark grey in color with an increase in bt and hbl. Fractures show chl alt'n, carb limited to a few selvages. Core is less broken. Few veins, but sulphide veinlets are common. Po is dominant sulphide at these depths, with minor cpy also present. Aspy can also be found in trace quantities.			1			
	EOH									

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 20 - 22, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages			% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																					B380570	STANDARD 4D		0.440	4D		VA05060563	
5	1	0.2	1.0	40		0.2	q	2	0				0.1								B380571	149.35	150.88	0.168			VA05058631	1.53
4	1	0.2	0.8	40		0.2	chl	3	0				0.1								B380572	150.88	151.49	0.104			VA05058631	0.61
2	1	2.0	2.5	40		0.2	q	3	0				3.0								B380573	151.49	152.40	0.200			VA05058631	0.91
4	1	0.2	0.8	40		0.2	q	3	0				3.0								B380574	152.40	153.92	0.149			VA05058631	1.52
4	6	0.5	2.0	50						100.0								30.0			B380575	153.92	155.45	0.142			VA05060563	1.53
4	1	0.5	1.1	40		1.0	k	4	0	5.0			3.0															
																					B380576	BLANK		<0.005			VA05060563	
8	1	1.0	2.4	40		2.0	k	4	0	0.1			5.0								B380577	155.45	156.97	0.068			VA05060563	1.52
3	1	0.5	0.9	40		0.2	k	4	0				1.0								B380578	156.97	157.74	0.066			VA05060563	0.77
1	1	0.2	0.2	40									0.1								B380579	157.74	158.50	0.034			VA05060563	0.76
2	1	0.2	0.2	40		0.2	q	2	0				0.1								B380580	158.50	160.02	0.049			VA05058631	1.52
																					B380581	160.02	161.54	0.046			VA05058631	1.52
																					B380582	160.02	161.54	0.060	DUP		VA05058631	1.52
4	1	0.2	0.8	40		0.2	q	3	0				0.1								B380583	161.54	163.07	0.090			VA05058631	1.53
4	1	0.5	1.1	40		0.2	k	4	0				0.1								B380584	163.07	164.59	0.056			VA05058631	1.52
7	1	0.2	1.4	40		0.2	q/k	3	0				3.0								B380585	164.59	166.12	0.059			VA05058631	1.53
2	6	0.2	0.4	40									100.0								B380586	166.12	167.64	0.046			VA05058631	1.52
3	1	1.0	1.4	40		1.0	q	3	0				1.0								B380587	167.64	169.16	0.054			VA05060563	1.52
1	1	1.0	1.0	40		0.2	chl	4	0				1.0								B380588	169.16	170.69	0.093			VA05060563	1.53
1	1	1.0	1.0	40		0.2	chl	4	0				1.0								B380589	169.16	170.69	0.077	PD/CA		VA05060563	1.53
																					B380590	STANDARD 4D		0.442	4D		VA05060563	
3	1	2.0	2.4	40	170	0.2	chl	4	0		3.0		1.0								B380591	170.69	172.21	0.072		po found in 170 deg vein	VA05060563	1.52
6	6	0.5	1.5	50									100.0								B380592	172.21	173.48	0.086			VA05060563	1.27
11	1	0.2	2.2	40		0.2	q	2	0				1.0								B380593	173.48	175.26	0.078			VA05060563	1.78
2	1	0.2	0.4	40		0.2	q	2	0				1.0								B380594	175.26	176.78	0.051			VA05060563	1.52
2	4	0.2	0.4	40																	B380595	176.79	178.31	0.036			VA05060563	1.52
																					B380596	BLANK		<0.005			VA05060563	
3	1	1.0	2.2	40		0.2	q	3	0				1.0								B380597	178.31	179.83	0.028			VA05060563	1.52
3	1	0.2	0.6	40		0.2	chl	2	0				1.0								B380598	179.83	181.36	0.092			VA05060563	1.53
2	6	0.2	0.4	40									100.0															
3	1	1.0	1.4	40		0.2	chl	3	0				3.0								B380599	181.36	182.88	0.043			VA05060563	1.52
2	1	0.2	0.4	40		0.2	q	3	0				0.1								B380600	182.88	184.40	0.029			VA05060563	1.52
3	6	0.2	6.0	40		0.2	q	3	0				100.0								B380601	184.40	185.93	0.028			VA05060563	1.53
3	6	0.2	6.0	40		0.2	q	3	0				100.0								B380602	184.40	185.93	0.054	DUP		VA05060563	1.53
2	6	0.2	0.4	40		0.2	q	3	0				100.0								B380603	185.93	187.45	0.047			VA05060563	1.52
2	1	0.2	0.2	40									0.1								B380604	187.45	188.98	0.019			VA05060563	1.53
3	1	0.2	0.6	40		0.2	q	4	0	1.0											B380605	188.98	190.50	0.028			VA05060563	1.52
3	1	0.5	0.9	40		0.2	q	2	0	15.0	5.0										B380606	190.50	192.02	0.019			VA05060563	1.52
5	1	0.2	1.0	40		0.2	q	2	0		10.0	1.0	0.1								B380607	192.02	193.55	0.027			VA05058631	1.53
3	1	0.2	0.6	40		0.5	q	3	0		3.0										B380608	193.55	195.37	0.026			VA05058631	1.52
3	1	0.2	0.6	40		0.5	q	3	0		3.0										B380609	193.55	195.37	0.028	PD/CA		VA05058631	1.52
																					B380610	STANDARD 2B		3.000	2B		VA05058631	
																					EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-289C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 961m

BEARING: 000 | DIP: -50°

DATE STARTED: 22-Jun-05 | DATE COMPLETED: 24-Jun-05

COORD SYSTEM: NAD 27: EASTING: 459560 NORTHING: 7099246

COORD SYSTEM: NAD 83: EASTING: 459442 NORTHING: 7099434

NAD 27 (CORRECTED for historic grid): EASTING: 459530 NORTHING: 7099256

LOGGED BY: Terry Croteau June 26-July 1, 2005

SECTION LINE(historic grid): 459530

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 7.01m

Deviation:

Casing: 7.01m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381684-B381716

Requisition #: MASP448STRGOL.05Q Date Shipped:

Lab Record #: VA05055279 Date Received: 8-Jul-05

Sample Sequence: B381717-B381878

Requisition #: MASP448STRGOL.05Q Date Shipped:

Lab Record #: VA05058632 & VA05060567 Date Received: 15-Jul-05 & 21-Jul-05

Special Note: Samples divided between lab records - most of hole between these two.

Duplicates:	381702; 381722; 381742; 381762; 381782; 381802; 381822; 381842; 381862
Preparation Duplicate/ Check Assay:	381689; 381709; 381729; 381749; 381769; 381789; 381809; 381829; 381849; 381869
Standards:	381690 (3C); 381710 (1A); 381730 (5E); 381750 (3C); 381770 (7G); 381790 (1A); 381810 (7G); 381830 (3C); 381850 (4D); 381870 (2B)
Blanks:	381696; 381716; 381736; 381756; 381776; 381796; 381816; 381836; 381856; 381876

FROM	TO	LITHOLOGY
0.00	7.01	Casing/OVB
7.01	53.64	MSED
53.64	207.26	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	340.7	61.0	006.7	007.7
150.0	345.1	61.2	011.1	012.1
207.26	346.0	61.4	012.0	013.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE	of 10
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 7.01			Casing/Overburden						
80	7.01 - 53.61			MSED: Variable composition/textures and mineralogy						
80		7.01	9.14	MSED rusty brown in color; Foliation at 30° TCA; Core very coherent and recovery is good: At 9.01m clayey gouge contains qtz eyes and MSED frags	2					
80		9.14	15.24	MSED core is broken into angular frags less than 8cm in diam; Poor recovery ~30%; At 11.69m, 5cm quartz vein at 50° TCA contains 5% aspy in fractures; Aspy appears to have weathered out of the remaining fractures.	1					
80		15.24	15.69	45cm clay gouge; Brown rusty color at 40° TCA; Contains qtz eyes and MSED frags; Adjacent rock is highly fractured and friable; Gouge is soft but coherent	3			4		
80		15.69	16.09	Broken rusty colored MSED; Limonite staining on fractures; Pieces <10cm	1					
80		16.09	17.89	MSED limonite staining on fracture; Foliation at 40°.	1					
80		17.89	20.12	Core is broken; Gravel size frags pervasive limonite and on fractures; At 19.43m, 38 cm gouge at 80° TCA, qtz eyes and MSED frags present	3					
80		20.12	20.71	MSED; Increase in competency and rec; Limonite stain on fractures only; Foliation at 45° TCA	1					
80		20.71	21.34	Core is composed of rounded MSED frags within a black matrix; Soft, altered to clays; Possible FAULT; No visible slip direction; Core crumbles if touched.	1					
80		21.34	23.62	MSED; Good recovery; Foliation at 40° TCA; Minor pervasive limonite; Limonite on fractures dominantly	2					
80		23.62	24.38	Core becomes fractured, recovery decreases; Broken fragments < 15cm; Foliation continues at 40° TCA	1					
80		24.38	27.80	Core regains competence; Good recovery; Limonite on fractures; Foliation still at 40° TCA; At 26.89m 15cm GND dyke at 40° TCA; At 27.23m 8cm GND dyke at 40° TCA						
80		27.80	28.79	MSED broken into gravel size fragments; Rounded; Limonite is pervasive; Quartz fragments indicate possible veins; At 28.1m, 8cm clayey gouge, contains quartz eyes.	3					
80		28.79	31.82	Core again competent with good recovery; Limonite on fracture faces; Foliation at 40° TCA; Quartz becoming interbedded in the MSED at 40°.						
80		31.82	32.25	Core is broken into gravel sized frags; Heavy limonite staining on fractures	2					
80		32.25	33.33	MSED: Competent fractures at 40° and 130° TCA; 130° cross cuts foliation running at 40°; minor staining on fractures faces.	1					
80		33.33	33.87	52cm gouge unit at 30° TCA crosscutting the foliation; Gouge contains qtz eyes and MSED frags; Minor limonite staining.	1					
80		33.87	40.24	Core becomes dark green-black MSED; Foliation is harder to distinguish, where visible it is at 40° TCA, but changes to 5° TCA and becomes crenulated at 36.69m; Foliation returns to 40° TCA at 37.23m; Fractures continue at 40° and 130° TCA.	1					
80		40.24	44.00	Core is fragmented with heavy limonite staining on fractures; Foliation at 40° TCA; At 43.89m 4cm GND dyke flanked by 1cm veins at 40° TCA						
80		44.00	44.85	Core is more competent; Limonite and sericite on fractures; Foliation at 40° TCA						
80		44.85	48.97	Core is again fragmented; Foliation is at 10° TCA; Minor limonite staining on fractures; 47.74 - 48.77m recovery is 10%						
80		48.97	53.49	MSED: Core is fractures and broken with sericite alteration and pervasive limonite foliation at 85° TCA; At 48.97m a 10cm clay gouge at 85° TCA contains qtz eyes and MSED frags; At 50.71m a 10cm clay gouge at 85° TCA contains qtz eyes and GND frags						
80		53.49	53.64	MSED/GND ctc; MSED is folded with qtz eyes, slickenslides present on fractures and contact; At 53.56m a 5cm black gouge composed of MSED frags, qtz eyes and GND frags						
10	53.64 - 207.26			GND: Fine to med grained; The majority of the veinage occurs after 67.2m						

DRILL LOG LEGEND P2

Selvages 0 = No Alteration, 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B381684	7.01	7.62	0.018			VA05055279	0.61
0																						B381685	7.62	9.14	0.052			VA05055279	1.52
0																						B381686	9.14	10.67	0.021			VA05055279	1.53
1	1	5.0	5.0	30		0.0							2.0					90.0				B381687	10.67	12.19	0.019			VA05055279	1.52
0																						B381688	12.19	13.72	0.005			VA05055279	1.53
0																						B381689	12.19	13.72	0.005	PD/CA		VA05055279	1.53
																						B381690	STANDARD 3C		0.094	3C		VA05055279	
0																						B381691	13.72	15.24	0.006			VA05055279	1.52
0																						B381692	15.24	15.69	0.053			VA05055279	0.45
0																						B381693	15.69	16.76	0.151			VA05055279	1.07
2	1	7.0	9.0	40		0.0					1.0							100				B381694	16.76	18.29	1.685			VA05055279	1.53
0																						B381695	18.29	19.81	0.053			VA05055279	1.52
																						B381696	BLANK		<0.005			VA05055279	
0																						B381697	19.81	20.71	0.064			VA05055279	0.9
																						B381698	20.71	21.34	0.051			VA05055279	0.63
3	1	7.2	7.0	50		0.0																B381699	21.34	22.86	0.715			VA05055279	1.52
2	1	0.2	0.9	50		0.0				1												B381700	22.86	24.38	0.254			VA05055279	1.52
1	1	2.0	2.0	60		0.0																B381701	24.38	25.91	0.349			VA05055279	1.53
1	1	2.0	2.0	60		0.0																B381702	24.38	25.91	0.185	DUP		VA05055279	1.53
2	1	0.2	0.4	50		0.0																B381703	25.91	27.43	0.060			VA05055279	1.52
1	1																					B381704	27.43	28.96	0.019			VA05055279	1.53
1	1	0.5	0.5	45		0.0																B381705	28.96	30.48	0.005			VA05055279	1.52
0																						B381706	30.48	32.00	0.084			VA05055279	1.52
1	6	0.2	0.2	40						100												B381707	32.00	33.33	0.009			VA05055279	1.33
0																						B381708	33.33	33.87	<0.005			VA05055279	0.54
0																						B381709	33.33	33.87	<0.005	PD/CA		VA05055279	0.54
																						B381710	STANDARD 1A		0.931	1A		VA05055279	
0																						B381711	33.87	35.05	0.006			VA05055279	1.18
2	1	4.0	8.0	50	20	0.0							1.0									B381712	35.05	36.58	3.600			VA05055279	1.53
2	1	1.5	2.0	20		0.0																B381713	36.58	38.10	1.365			VA05055279	1.52
1	1	2.5	2.5	45		0.0																B381714	38.10	39.62	0.024			VA05055279	1.52
1	1	8.0	8.0	40		0.0				0.1			1.0									B381715	39.62	41.15	0.040			VA05055279	1.53
0																						B381716	BLANK		<0.005			VA05055279	
																						B381717	41.15	42.67	0.082			VA05058632	1.52
3	1	1.0	3.0	40		0.0																B381718	42.67	44.20	0.034			VA05058632	1.53
1	1	7.0	7.0	40		0.0																B381719	44.20	45.72	0.278			VA05058632	1.52
0																						B381720	45.72	47.24	0.098			VA05058632	1.52
0																						B381721	47.24	48.77	0.035			VA05058632	1.53
0																						B381722	47.24	48.77	1.845	DUP		VA05058632	1.53
0																						B381723	48.77	50.29	0.051			VA05058632	1.52
																						B381724	50.29	51.82	0.252			VA05058632	1.53
																						B381725	51.82	53.34	0.508			VA05060567	1.52
1	1	0.5	0.5	45		1.0	q	3	0													B381726	53.34	53.64	0.064			VA05060567	0.3

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE 3 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		53.64	60.56	Moderately broken altered GND; Hematite is pervasive and on fractures; Fractures occur at 45° and 80° TCA; Core is highly fractured and broken; Minor clay alteration on fractures; At 59.44m sugary texture intersected by 9cm qtz veins	2			1		
10		60.56	63.79	Core is still fractured and broken; but pervasive limonite is reduced as well; Less on fractures; Also, very little clay alteration; At 61.3m to 62m minor clay alteration on fractures	1					
10		63.79	66.56	GND is grey in color and altered to sericite; Texture is soft but coherent; Core is permeable; Recovery is poor; Fracture angles observed by texture.	2	2		1		
10		66.56	88.92	Unaltered GND; Pervasive Limonite is absent, found only on fractures; Fractures at 40° and 110° TCA; Carbonate also found on fractures; Recovery is good; At 73.15m minor sericite on fractures; At 76.95m, 7cm qtz vein at 60° TCA; At 77.03m, 6cm qtz veins at 60° TCA; At 88.29m, a 6cm qtz vein at 30° TCA; At 88.89m, 8cm qtz vein at 30° TCA; Veining increases in size after 75.65m as well as in frequency; Sulphides begin to appear in veins; The majority is aspy with minor py; Most veins contain only trace amounts of either sulphide.	1					
10		88.92	92.96	Unaltered GND; Limonite no longer present in any form; GND is dark grey with increased veinage.		1				
10		92.96	93.76	GND is greenish grey; Mafics almost totally absent; Chl alteration dominant; Possibly a large selvage; At 92.46m, 2cm clay gouge at 40° TCA			2			
10		93.76	96.01	Unaltered GND; Fractures at 60° and 120°; Reduction in number and frequency of veins; GND is still dark grey.						
10		96.01	96.61	Core is light grey to green; Sericite and chlorite alteration present; Metased xenolith at 96.13 to 96.50m; 4cm grey gouge at 45° TCA, 2cm rusty stain of hematite.		1	2	1		
10		96.61	103.63	Unaltered GND; Fractures at 30° and 100° TCA; Carbonate present on most veins; Disseminated pyrite found at 102.11m; Possible fine grained VG(?)						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5																				B381727	53.64	54.86	0.076			VA05060567	1.22
1	1	0.2	0.2	30									0.1									B381728	54.86	56.39	0.081			VA05060567	1.53
1	1	0.2	0.2	30									0.1									B381729	54.86	56.39	0.098	PD/CA		VA05060567	1.53
																						B381730	STANDARD 5E		1.415	5E		VA05060567	
0																						B381731	56.39	57.91	0.095			VA05060567	1.52
3	1	2.0	4.2	45	10	0.0							0.1									B381732	57.91	59.44	0.200			VA05060567	1.53
1	1	10.0	10.0	45		0.0																B381733	59.44	59.62	0.073			VA05060567	0.18
0																						B381734	59.62	60.96	0.041			VA05060567	1.34
																						B381735	60.96	62.48	1.085			VA05060567	1.52
1	1	1.5	5.0										0.1									B381736	BLANK		<0.005			VA05060567	
																						B381737	62.48	64.01	2.150			VA05060567	1.53
1	1	2.0	2.0																			B381738	64.01	65.53	1.775			VA05060567	1.52
2	1	0.2	0.2	45		0.0																B381739	65.53	67.06	0.025			VA05060567	1.53
1	1	1.5	1.5	30		0.0							1.0									B381740	67.06	68.58	0.084			VA05060567	1.52
2	1	2.0	4.0	20		0.0							1.0									B381741	68.58	70.10	0.054			VA05058632	1.52
2	1	2.0	4.0	20		0.0							1.0									B381742	68.58	70.10	0.342	DUP		VA05058632	1.52
3	1	0.5	0.9	40		0.0					1.0											B381743	70.10	71.63	0.010			VA05058632	1.53
2	1	0.5	0.7	40		0.0																B381744	71.63	73.15	0.047			VA05058632	1.52
1	6	0.2	0.2	15									100					60.0	10			B381745	73.15	74.68	0.075			VA05058632	1.53
3	1	1.0	2.0	35		0.0				2												B381746	74.68	75.65	0.061			VA05058632	0.97
3	1	3.0	8.0	35		0.0				2												B381747	75.65	76.20	0.204			VA05058632	0.55
3	1	1.2	2.0	30		0.0							0.1									B381748	76.20	77.72	0.070		Euhedral aspy on fract surf	VA05058632	1.52
3	1	1.2	2.0	30		0.0							0.1									B381749	76.20	77.72	0.065	PD/CA		VA05058632	1.52
																						B381750	STANDARD 3C		0.094	3C		VA05058632	
2	1	0.2	0.4	40		0.0					0.1											B381751	77.72	79.25	0.009			VA05058632	1.53
4	0	0.5	1.1	40		1.0	chl	3	0				0.1									B381752	79.25	80.77	0.070			VA05058632	1.52
3	1	0.2	0.6	35							0.1		0.1									B381753	80.77	82.30	0.100			VA05058632	1.53
4	1	1.0	1.5	40							0.1											B381754	82.30	83.82	0.148			VA05058632	1.52
5	1	1.5	4.0			0.2	q	3	0				1.0									B381755	83.82	85.34	0.102			VA05058632	1.52
																						B381756	BLANK		<0.005			VA05058632	
2	1	1.0	1.2	40																		B381757	85.34	86.87	0.073			VA05058632	1.53
3	1	0.2	0.6	40	10	0.2	q/chl	3	0				5.0									B381758	86.87	87.89	0.098			VA05058632	1.02
3	1	9.0	17.0	40		1.0	q/chl	3	0				3.0									B381759	87.89	88.49	1.210			VA05058632	0.6
4	1	3.0	5.0	40							0.1											B381760	88.49	88.92	0.046			VA05058632	0.43
4	1	2.0	5.0	50		2.0	chl	2	0	0.1	0.1											B381761	88.92	91.44	0.081			VA05058632	1.52
4	1	2.0	5.0	50		2.0	chl	2	0	0.1	0.1											B381762	88.92	91.44	0.066	DUP		VA05058632	1.52
8	1	5.0	13.0	40		1.0	q	3	0		0.1		3.0									B381763	91.44	92.96	0.154			VA05058632	1.52
4	1	6.0	30.0			0.0							5.0									B381764	92.96	93.76	0.547			VA05060567	0.8
1	1	1.5	1.5	35		0.0				1			1.0									B381765	93.76	94.48	0.049			VA05060567	0.72
4	1	1.0	3.0	35		0.0							1.0									B381766	94.48	96.01	0.078			VA05060567	1.53
0																						B381767	96.01	96.61	0.165			VA05060567	0.6
2	1	1.0	1.5	40	10	0.0					0.1		0.1									B381768	96.61	97.54	0.248			VA05060567	0.93
2	1	1.0	1.5	40	10	0.0					0.1		0.1									B381769	96.61	97.54	0.236	PD/CA		VA05060567	0.93
																						B381770	STANDARD 7G		4.340	7G		VA05060567	
1	1	0.2	0.2	35		0.0							15									B381771	97.54	99.06	0.056			VA05060567	1.52
2	1	0.2	1.2	5	35	0.0				0.1			1.0									B381772	99.06	100.58	0.042			VA05060567	1.52
2	1	1.0	1.2	35		1.0	chl	3	0				3.0									B381773	100.58	102.11	0.136			VA05060567	1.53
1	1	0.2	0.2	35		0.0				5	15.0											B381774	102.11	103.63	0.169			VA05058632	1.52

DRILL LOG LEGEND - P1	DATE: June 22 - 24, 2005	PAGE 5 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 50; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		103.63	111.25	Unaltered GND; Good recovery; Fractures are at 35° and 110° TCA; Color is lighter grey than previous; Sulphides increase in concentration with po and cpy as dominant sulphides; Diss py and aspy still present on fractures; Fine grained, difficult to distinguish with hand lens; May be fine grained gold (?) present; The fractures containing sulphides also show slickenslides beneath.						
10		111.25	116.71	Unaltered GND; Light grey, becoming med grained; Fractures at 50° and 80° TCA; Po and aspy dominate vein sulphides; Trace disseminated aspy still present; At 113.38m 4cm gouge at 85° TCA; At 117.05m aspy showing slickenslides.						
10		116.71	120.40	GND is light green color and scratches easily; core is highly fractures and broken; Fractures occur at 50°, 80°, and 110° TCA; Pieces range from gravel size to >10cm; 50° fractures frequently contain slicks, but no mineralization.		1	1			
10		120.40	128.02	Unaltered GND, grey, fine grained; There is less mineralization present in the veins, but aspy is now present disseminated in the selvages.						
10		128.02	130.66	Unaltered GND; Decrease in veins and mineralization. Good recovery; Aspy found on slickenslides on fracture surfaces; Fractures at 30°, 60° and 120°.						
10		130.66	134.11	Chlorite alteration as well as sericite alteration on fractures; The number of veins increases as does mineralization; Core is broken with most fractures random; recovery is less than previous interval.		1	1			
10		134.11	135.36	Core is green, more chlorite alteration and an increase in the size of veins; This is also the start of a 10.32m zone of intense veining, alteration and mineralization at 135.36m		1	2			
10		135.36	135.64	28cm qtz vein; Total length may be greater as it was found at the end of run; Contact at 20° TCA; Fractures are filled with pyrite ~ 20%		2	3			
10		135.64	136.36	32cm qtz vein at 30° TCA, fractures filled with massive aspy; Selvage contains diss disseminated py						
10		136.36	137.86	Chlorite alteration is more intense; Core is highly fractured with clay in fractures; Quartz veins also fractured; Aspy fills fractures between qtz and altered GND		1	3			
10		137.86	138.16	Massive sulphide vein at 10° TCA; Composed of Aspy 70% oxidized; In 30cm quartz vein at 30° TCA; Py in qtz vein fracture						
10		138.16	139.40	Intensely altered GND; core is soft but competent; Clay and chlorite alteration; Quartz eyes and GND frags present; Disseminated aspy throughout						
10		139.40	139.96	56+cm quartz vein; vein is broken at both ends, and in the middle, true length may be greater, angle cannot be determined; Fractures are filled with massive aspy; Trace VG (?)						
10		139.96	141.73	GND; Altered chlorite and sericite; recovery good; Light green color; Disseminated pyrite found throughout, and in fractures						
10		141.73	145.60	Core is darker green color; Highly fractured and broken; Pieces range from gravel size to 20cm; Fractures continue to be filled with sulphides: aspy and py.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.5	3.0	45		1.0	chl	3	0	0.1	3.0		1.0									B381775	103.63	105.16	0.450			VA05058632	1.53
																						B381776	BLANK		<0.005			VA05058632	
3	1	2.0	5.0	25		1.0	q	3	0	0.1	1.0	0.1	1.0									B381777	105.16	105.76	0.702			VA05058632	0.6
0																						B381778	105.76	106.68	0.356			VA05058632	0.92
2	1	6.0	7.0	50		0.0					15.0	3.0				0.5						B381779	106.68	107.18	0.968		1mm vg found in split core in cpy	VA05058632	0.5
2	1	0.2	0.4	20		0.2	q	3	0				0.1									B381780	107.18	108.20	0.528			VA05058632	1.02
4	1	1.0	2.5	30		0.2	q	3	0	5	3.0		1.0									B381781	108.20	109.73	0.928			VA05060567	1.53
4	1	1.0	2.5	30		0.2	q	3	0	5	3.0		1.0									B381782	108.20	109.73	0.987	DUP		VA05060567	1.53
4	1	1.0	2.5	30		0.5	cb	3	0	3	5.0		1.0									B381783	109.73	111.25	0.074			VA05060567	1.52
1	1	3.0	3.0	40							1.0	0.1										B381784	111.25	112.78	0.112			VA05060567	1.53
1	1	2.0	1.0	60							3.0	1.5										B381785	112.78	114.00	0.212			VA05058632	1.22
5	1	2.0	9.0	55							50.0	0.1	5.0									B381786	114.00	114.80	1.915			VA05058632	0.8
2	1	1.0	1.5	55	10						1.0		0.1									B381787	114.80	115.87	0.129			VA05058632	1.07
2	1	0.2	0.4	55							0.1											B381788	115.87	117.35	0.513			VA05058632	1.48
2	1	0.2	0.4	55							0.1											B381789	115.87	117.35	0.139	PD/CA		VA05060567	1.48
																						B381790	STANDARD 1A		0.933	1A		VA05060567	
1	1	0.2	0.2	55									0.1									B381791	117.35	118.87	0.250			VA05060567	1.52
6	1	2.0	5.0	30		1.0	chl	3	0				5.0									B381792	118.87	120.40	0.221			VA05060567	1.53
2	1	2.0	2.5	30		1.0	q	3	0		0.1											B381793	120.40	121.92	0.081			VA05060567	1.52
2	1	1.0	1.5	30		3.0	chl	3	0		0.1		1.0									B381794	121.92	123.44	0.134			VA05058632	1.52
2	1	1.0	1.5	30		2.0	chl	3	0	1								10.0				B381795	123.44	124.97	0.225			VA05058632	1.53
																						B381796	BLANK		<0.005			VA05058632	
3	1	0.1	2.5	30		4.0	chl	3	0		1.0											B381797	124.97	126.49	0.090			VA05058632	1.52
4	1	1.5	3.0	30		3.0	chl	3	0				0.1									B381798	126.49	128.07	0.434			VA05060567	1.58
1	1	1.0	1.0	30		0.0				0.1												B381799	128.07	129.54	0.151			VA05060567	1.47
1	1	0.2	0.2	15																		B381800	129.54	130.66	0.120			VA05060567	1.12
0																						B381801	130.66	131.06	1.135			VA05060567	0.4
0																						B381802	130.66	131.06	0.451	DUP		VA05060567	0.4
																						B381803	131.06	132.59	4.770			VA05060567	1.53
2	1	1.0	1.5	30	165					1			1.0									B381804	132.59	134.11	0.469			VA05060567	1.52
4	1	6.0	9.5	15		5.0	chl	4	0	5			5.0									B381805	134.11	135.36	0.720			VA05060567	1.25
1	1	28.0	28.0	20						20						0.2						B381806	135.36	135.64	7.090		Tr vg found in split core	VA05060567	0.28
0																						B381807	135.64	136.04	2.590			VA05060567	0.4
1	1	32.0	32.0	30						1			10					60.0				B381808	136.04	136.36	14.250			VA05060567	0.32
1	1	32.0	32.0	30						1			10					60.0				B381809	136.04	136.36	16.050	PD/CA		VA05060567	0.32
																						B381810	STANDARD 7G		4.740	7G		VA05060567	
																						B381811	136.36	137.86	2.140			VA05060567	1.5
1	1	30.0	30.0	30		0.0				5			1									B381812	137.86	138.16	14.250			VA05060567	0.3
1	6	2.0	2.0	10		0.0							100					70.0											
0																						B381813	138.16	139.40	5.570			VA05060567	1.24
1	1	56.0	56.0							3			15			0.1						B381814	139.40	139.96	14.000		Trace VG	VA05058632	0.56
2	1	2.0	3.0	30		3.0	chl	3	0	3												B381815	139.96	141.17	0.977			VA05058632	1.21
																						B381816	BLANK		0.008			VA05058632	
0																						B381817	141.17	142.31	0.008			VA05058632	1.14
3	1	3.0	5.0	30		4.0	chl	4	0	0.1			10			0.1						B381818	142.31	143.26	1.805			VA05058632	0.95
4	1	7.0	9.0	150	60	2.0	chl	3	0	3			1.0					40.0				B381819	143.26	144.78	0.219			VA05060567	1.52
5	1	9.0	17.5	150	60	5.0	chl	3	0	10			3.0					40.0				B381820	144.78	145.60	1.210			VA05060567	0.82

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE 7 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		145.60	147.82	GND shown significantly less alteration being present; Mostly as vein selvages; Mineralization is reduced and core is more competent; Recovery is very good.			1			
10		147.82	155.77	Slightly altered GND; Core is dark grey/green; Core is highly fractured and broken; Recovery is less than previous; Po returns in veins. @151.14m, clay gouge at 30° TCA; 2cm gouge is followed by a broken qtz vein in deformed GND; Fracture face shows pyrite with slickenslides; Small fault, core is too broken to get width.			1			
10		155.77	161.54	Core is again green with chlorite; It is competent with good recovery; Quartz and carbonate mottle the core; Quartz veins are deformed, broken and fractured; Carbonate fills fractures, as well as possible tension gashes; At 160.97m qtz crystals show foliation direction at 45° TCA; Possible shear; Sulphides are found bordering carbonate filled fractures and gashes; Slickenslides present on some fractures.			3			
10		161.54	162.04	FAULT ZONE: Deformation is most intense; Fault is composed of black clay filled with porphyroclasts and quartz eyes in S-fabric indicates sinistral movement; Contact at 45° TCA; Py in fractures; At 161.94m fault gouge, 10cm, w/ quartz eyes.				5		
10		162.04	166.12	GND is moderately alt'd, pale green color. Highly fractured and broken w/ most of the core being gravel-sized w/ 10% being up to 10cm. Chl & ser alt'n on fracs. Some fracs filled w/ py. Recovery is less.		2	2			
10		166.12	170.69	Core shows similar alt'n but is more competent. Gravel-sized pieces are almost absent, w/ 85% greater than 10cm.		2	2			
10		170.69	175.26	Core becomes fractured and broken to gravel size pieces. Clay alt'n on frac increases. Decrease in vn size and frags. Core is light grey in color, med gr, dissem po present.		1	1	2		
10		175.26	176.78	Core changes to white-green in color and becomes broken. Carbonate alt'n dominant. Carb also found on frac faces.			2		3	
10		176.78	177.23	Core is alt'd heavily to clay; soft but competent. Qtz eyes and GND frags present. @177.12m: 30° contact w/ possible small (~2cm) fault. Qtz appears to show 30° foliation, contact @ black clay w/ py filled frac.						
10		177.23	179.64	Ser and chl alt'n in the form of selvages only. Alt'n of frac srfc's is limited to minor carb ~30°.						
10		179.64	182.38	Return to dark grey, unalt'd GND. Core is still fractured and broken, but recovery has increased. Fracs normally @60°. Po returns in vns.						
10		182.38	183.14	Core is light green colour, w/ ser alt'n on frac. @182.62m: ~2cm gouge @ 45° to CA, filled w/ black clay and massive py. Slickensides present.		1	2			
10		183.14	184.40	Clay alt'n increased, especially on fracs. Core crumbles when handled.				3		
10		184.40	185.63	Light green color, increased competence and recovery. @185.20m: 2cm sulphide vn @50° to CA; contact between chl and ser alt'n. Ser fills frac around round xenoliths of chl alt'd GND. Looks like a conglomerate.		2	2			
10		185.63	186.72	Grey GND, frac & broken frac @60° and 140°, less chl and ser.			1			
10		186.72	190.80	GND is more competent, better recovery. Clay alt'n is higher and core can be easily broken. Soft but coherent. Fracs @50° and 110°. Core is light grey color.		1	1	3		
10		190.80	192.87	Core is broken into gravel-sized pieces (80%) and frags >7cm. Less recovery, core is dark grey.				1		

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

PAGE 8 of 10

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	4	0.5	1.0	70																		B381821	145.60	146.30	0.030			VA05060567	0.7
2	4	0.5	1.0	70																		B381822	145.60	146.30	0.025	DUP		VA05060567	0.7
2	1	1.0	1.2	30	175	0.2	q	3	0	1												B381823	146.30	147.82	0.103			VA05060567	1.52
1	1	0.2	0.2	30		0.2	q	3	0		0.1											B381824	147.82	149.35	0.066			VA05058632	1.53
1	1	0.2	0.2	30		0.2	q	3	0		0.1											B381825	149.35	150.88	0.062			VA05058632	1.53
2	1	2.0	2.5	30									15									B381826	150.88	152.40	0.432			VA05058632	1.52
2	1	1.0	2.0	30									1.0									B381827	152.40	153.92	0.077			VA05058632	1.52
1	1	1.0	1.0	30									0.1									B381828	153.92	155.45	0.045			VA05058632	1.53
1	1	1.0	1.0	30									0.1									B381829	153.92	155.45	0.046	PD/CA		VA05058632	1.53
																						B381830	STANDARD 3C		0.094	3C		VA05058632	
3	1	1.0	1.5	4	30		0.2	cb	3	0			0.1									B381831	155.45	156.97	0.243			VA05058632	1.52
3	1	1.5	4.0																			B381832	156.97	158.50	0.126			VA05060567	1.53
	4												1.0																
4	1												1.0									B381833	158.50	160.02	0.143		vns too deformed for measurement	VA05060567	1.52
2	1												1.0									B381834	160.02	161.54	0.394		same as above	VA05060567	1.52
0																						B381835	161.54	162.04	0.325			VA05058632	.0.5
																						B381836	BLANK		<0.005			VA05058632	
3	1																					B381837	162.04	163.07	2.190		vns are broken	VA05058632	1.03
3	1																					B381838	163.07	164.59	0.918		vns are broken	VA05058632	1.52
2	1	2.0	3.0	30		0.2	chl	3	0			0.1										B381839	164.59	166.12	0.138			VA05060567	1.53
2	1	1.0	1.2	30	10					0.1												B381840	166.12	167.64	1.390			VA05060567	1.52
0																						B381841	167.64	169.16	0.581			VA05060567	1.52
0																						B381842	167.64	169.16	0.847	DUP		VA05058632	1.52
2	1	1.0	1.0	30		0.2	qtz	0	0				1.0									B381843	169.16	170.69	0.276			VA05058632	1.53
1	1	1.0	1.0	30									0.1									B381844	170.69	172.21	0.107			VA05058632	1.52
1	1	1.0	1.0	30							1.0											B381845	172.21	173.74	0.265			VA05060567	1.53
4	1												1.0									B381846	173.74	175.26	0.644		vns are broken	VA05060567	1.52
2	1	1.5	1.7	30		4.0	chl	3	0	1			0.1									B381847	175.26	176.78	0.569			VA05060567	1.52
0																						B381848	176.78	177.23	0.196			VA05060567	0.45
0																						B381849	176.78	177.23	0.116	PD/CA		VA05060567	0.45
																						B381850	STANDARD 4D		0.443	4D		VA05060567	
4	1	0.2	0.8	50						0.1			0.1									B381851	177.23	178.31	0.120			VA05060567	1.08
2	1	0.5	1.0	30									0.1									B381852	178.31	179.83	0.301			VA05060567	1.52
2	1	0.5	0.7	30							0.1	0.1	0.1									B381853	179.83	181.36	0.123			VA05060567	1.53
2	1	0.2	0.4	30								0.1	0.1									B381854	181.36	182.38	0.697			VA05060567	1.02
0																						B381855	182.38	183.14	1.535			VA05060567	0.76
																						B381856	BLANK		<0.005			VA05060567	
2	1	0.2	0.4	85						1												B381857	183.14	184.40	0.136			VA05060567	1.26
3	1	0.2	0.6	50						0.1												B381858	184.40	185.13	0.431			VA05060567	0.73
3	6	0.2	0.6	45		0.0				100								30.0				B381859	185.13	185.63	4.680			VA05060567	0.5
1	1	0.2	0.2	50		0.0																B381860	185.63	186.72	0.557			VA05060567	1.09
1	1	1.0	1.0	40		0.0							0.1									B381861	186.72	187.45	0.844			VA05060567	0.73
1	1	1.0	1.0	40		0.0							0.1									B381862	186.72	187.45	4.950	DUP		VA05060567	0.73
1	1	1.0	1.0	40		0.0							0.1									B381863	187.45	188.98	0.470			VA05060567	1.53
2	1	0.5	0.7	70		0.0																B381864	188.98	190.50	0.360			VA05060567	1.52
2	1	0.2	0.4	75		0.2	cb	3	0	0.1												B381865	190.50	192.02	0.532			VA05060567	1.52

DRILL LOG LEGEND P1	DATE: June 22 - 24, 2005	PAGE 9 of 10	
DRILL HOLE # : DG05-289C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		192.87	198.12	Return to clay alt'n. Core is soft but coherent, better recovery. Frac angles are difficult to obtain due to alt'n on frac, but appear to be @55° and 110°.		1	1	3		
10		198.12	200.07	Core is still soft but coherent. Many fracs are filled w/ black clay @199.39m, ~30cm. Qtz eyes and frags present between clay layers. Possible winged porphyroblast. This may be a fault. GND is white-light grey.		1	1	4		
10		200.07	205.74	At 35° contact w/ white GND at 0.5cm carb vn. GND is grey to dark grey. Competence increased and good recovery. Alt'n is limited to minor chl on frac faces. Frac at 10° and 30°, med gr.						
10		205.74	207.26	GND becomes darker grey, finer-grained.						
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 22 - 24, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	2.0	2.4	60		0.2	cb	3	0		1.0											B381866	192.02	193.55	**2.240**			VA05060567	1.53
3	1	0.2	0.6	60		0.0							0.1									B381867	193.55	195.07	**1.035**			VA05058632	1.52
1	6	0.5	0.5	80		0.0							100					10.0											
1	1	0.2	0.2	60		0.0							0.1									B381868	195.07	196.60	**0.743**			VA05058632	1.53
1	1	0.2	0.2	60		0.0							0.1									B381869	195.07	196.60	**0.665**	PD/CA		VA05058632	1.53
																						B381870	STANDARD 2B		**3.010**	2B		VA05058632	
3	1	1.5	1.9	60		0.0																B381871	196.60	198.12	**2.150**			VA05058632	1.52
0																						B381872	198.12	199.69	**0.593**			VA05060567	1.57
1	4	0.5	0.5	35		0.0																B381873	199.69	201.17	**0.202**			VA05060567	1.48
3	1	1.0	1.4	60	80	0.0				0.1												B381874	201.17	202.69	**0.246**		2% moly in vns	VA05060567	1.52
2	1	0.5	0.7	60		0.0																B381875	202.69	204.22	**0.329**			VA05060567	1.53
																						B381876	BLANK		**<0.005**			VA05060567	
0																						B381877	204.22	205.74	**0.373**			VA05060567	1.52
0																						B381878	205.74	207.26	**0.319**			VA05060567	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-290C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 905m

BEARING: 180 | DIP: -50°

DATE STARTED: 23-Jun-05 | DATE COMPLETED: 26-Jun-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459109 NORTHING: 7099040

COORD SYSTEM: NAD 83: EASTING: 4598991 NORTHING: 7099224

NAD 27 (CORRECTED for historic grid): EASTING: 459079 NORTHING: 7099050

SECTION LINE(historic grid): 459079E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 4.57m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381927 - B382075 and B382080 - B382098

Requisition #: MASP448STRGOL.05Q | Date Shipped: 8-Jul-05

Lab Record #: VA05060235, VA05058633 (alternating) | Date Received: 21-Jul-05, 15-Jul-05

Sample Sequence: B382076 - B382079

Requisition #: MASP448STRGOL.05Q | Date Shipped: 8-Jul-05

Lab Record #: VA05060567 | Date Received: 21-Jul-05

Sample Sequence: BB382099 - B382156

Requisition #: MASP448STRGOL.05Q | Date Shipped: 10-Jul-05

Lab Record #: VA05060237, VA05058634 (alternating) | Date Received: 21-Jul-05, 15-Jul-05

Duplicates:	B381942, B381962, B381982, B382002, B382022, B382042, B382062, B382082, B382102, B382122, B382142
Preparation Duplicate/ Check Assay:	B381929, B381949, B381969, B381989, B382009, B382029, B382049, B382069, B382089, B382109, B382129, B382149
Standards:	B381930 (3C), B381950 (5E), B381970 (7G), B381990 (2B), B382010 (6F), B382030 (6F), B382050 (1A), B382070 (5E), B382090 (7G), B382110 (1A), B382130 (4D), B382150 (7G)
Blanks:	B381936, B381956, B381976, B381996, B382016, B382036, B382056, B382076, B382096, B382116, B382136, B382156

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	149.4	-51.4	175.4	176.4
125.0	146.4	-52.6	172.4	173.4
197.0	146.9	-53.2	172.9	173.9

FROM	TO	THOLOGY
4.57	4.75	Schistose Argillite
4.75	22.50	GND, varying degrees of alt'n
22.50	24.38	Sand/Gravel
24.38	29.96	GND, varying degrees of alt'n
29.96	29.14	Beach Sand
29.14	30.50	GND, varying degrees of alt'n
30.50	30.60	Variable Pebbles and Sand
30.60	32.00	GND, varying degrees of alt'n
32.00	32.30	Sand
32.30	196.60	GND, varying degrees of alt'n

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 4-8, 2005 PAGE 1 of 16		
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-4.57	0.00	4.57	Casing--No recovery (casing to 4.75m w/ recovery)..						
80	4.57-4.75	4.57	4.75	Schistose argillite. Fine laminations (meta-seds), denoted by layered micas-musc & bt.	0	0	1	0	0	
10	4.75-22.50	4.75	5.60	GND, relatively competent. Unalt'd btwn vnlets, covered w/ limonite-selvages up to 0.5cm wide. Broken on vnlets.	1	0	1	0	1	
10		5.60	15.00	Brown, crumbly, limonized GND. Lim is pervasive. whole rock appears oxidized; largest core pc is ~8cm long. Most <2cm in diameter. Reduced to coarse sand @ 7.0m, for 20cm. Ave recovery for this section is 33.8%.	4	1	1	3	2	
10		15.00	20.15	More competent GND infused w/ zoned k-spar/qtz vns. These k-spar/qtz vns' zonation is highlighted by 1-2mm wide layers of oxidized hematite, producing a rosy red/deep orange color, which appears to pervade the whole rock. Also throughout is minor chlorite alt'n and silicification. From 15.86m-19.81m: vns are not clearly visible (only few small ones), but rock is still extensively hem & lim stained and alt'd. Slickensides on 45° face w/in clay alt'd section, 20cm wide at 17.3m.	4	2	3	2	2	
10		20.15	22.20	Highly alt'd GND; 90% GND texture is erased to fine-gr, v. colourful rock. Colors due to chl, lim, clay weathering (white-yellow), ox'd sulphides (black).	4	3	3	4	1	
10		22.20	22.50	Bleached, soft GND. Texture normal (visible grains), but more crumbly and broken up.	2	0	0	2	0	
1	22.50-24.38	22.50	24.38	Highly alt'd, broken up to crumbly to coarse sand-sized pc's. Hematite staining also continues, through 40% of section. Lim staining through all, and covering frac srfc's. Pocket of clean 'beach' sand at 22.86m-23.0m, hypotheses to follow @ 29.14m.	4	0	2	1	0	
10	24.38-28.96	24.38	28.96	Drastic change in lithological alt'n to pale bluish white, crumbly, clay & chl alt'd GND. @26.8m: sulphide vn is 80% ox'd py, 20% aspy in slickenside form.	0	4	3	3	0	
1	28.96-29.14	28.96	29.14	Light to med brown sand, size 1mm grains of bt, qtz, feldsp. Well-sorted beach sand. Origin unknown. Ideas: (1) Frac infill; (2)Ground up GND then washed w/ water (but no evidence of frac or fault); (3)Contamination from above in hole (but no record of problem from drill). Three more zones of washed sand/gravel in hole as well, w/in 15m zone.	1	0	0	0	0	
10	29.14-30.50	29.14	30.50	Clay/chl alt'd GND as previous to sand.						
1	30.50-30.60	30.50	30.60	Subangular to subrounded pebbles-cobbles of metaseds (50%) and pure qtz (30%). 20% silty sand, med brown.						
10	30.60-32.00	30.60	32.00	Clay/chl'd GND as before pebbles	0	4	3	4	0	
1	32.00-32.30	32.00	32.30	Light to med brown sand, well-sorted except first 5cm has dark grey clay (30%). Parts up to 10cm long were core-shaped but not competent.						
10	32.30-196.90	32.30	34.00	Sericitized GND, orig texture 80% erased. Evidence of shear; slickensides shown on frac faces & w/in soft, alt'd zones; shown in feldspars (plagioclase) and sericite.	0	4	1	2	0	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

PAGE 2 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	2.0	2.0																			B381927	4.57	4.75	0.006		qtz pc's	VA05060235	0.18
1	6	0.3	0.3	20		0				20			60.0					4.0	0.0			B381928	4.75	5.60	0.038			VA05060235	0.85
1	6	0.3	0.3	20		0				20			60.0					4.0	0.0			B381929	4.75	5.60	0.036	PD/CA		VA05060235	0.85
																						B381930	STANDARD 3C		0.094	3C		VA05060235	
0																						B381931	5.60	6.10	0.022			VA05060235	0.50
0																						B381932	6.10	7.62	0.042			VA05060235	1.52
0																						B381933	7.62	9.14	0.012			VA05060235	1.52
0																						B381934	9.14	10.67	0.018			VA05060235	1.53
2	1	0.5	1.0	65		4	qtz	2	3													B381935	10.67	12.19	0.037			VA05060235	1.52
							chl	1														B381936	BLANK		<0.005			VA05060235	
0																						B381937	12.19	13.72	0.023			VA05060235	1.53
2	1	0.4	0.7			100	s/chl	4,1	3					0.1								B381938	13.72	15.00	0.021		crumbly pc's	VA05060235	1.28
							q/cb	1,3																					
3	2	1.0	2.0	10	40	10	q/k	2	1													B381939	15.00	15.85	0.020			VA05060235	0.85
							chl	1																					
1	1	0.7	0.7	45		5	q/chl	1,2	3					2.0															
																						B381940	15.85	16.76	0.027			VA05060235	0.91
	6	0.3	0.3	30		1.5	q/cb	2	3	60								5.0				B381941	16.76	18.29	0.066			VA05060235	1.53
1	6	0.3	0.3	30		1.5	q/cb	2	3	60								5.0				B381942	16.76	18.29	0.071	DUP		VA05060235	1.53
1	6	0.4	0.4	15		3	qtz	3	4	60								5.0				B381943	18.29	19.81	0.030			VA05060235	1.52
1	1	0.6	0.6	60		10	q/cb	2	2	15								4.0											
0																						B381944	19.81	20.15	0.010			VA05060235	0.34
2	1	0.4	0.8	20		0				15								5.0				B381945	20.15	21.34	0.071			VA05060235	1.19
0																						B381946	21.34	22.20	0.115			VA05060235	0.86
1	1	0.3	0.3	20		10	qtz	2	3	5								5.0				B381947	22.20	22.50	0.017		loose pebbles	VA05060235	0.30
0																						B381948	22.50	23.70	0.218			VA05060235	1.20
0																						B381949	22.50	23.70	0.250	PD/CA		VA05058633	1.20
																						B381950	STANDARD 5E		1.475	5E		VA05058633	
0																						B381951	23.70	24.38	0.025			VA05058633	0.68
0																						B381952	24.38	25.91	0.024			VA05058633	1.53
1	6	0.2	0.2	40		2	chl/s	3,4	0	80			10.0					5.0	0.0			B381953	25.91	27.43	0.038			VA05058633	1.52
1	2	0.5	0.5			15	chl/s	3,4	0	0																		crumbly pc's		
2	1	0.5	1.0	45		1	q/s	2,3	0	5			10.0					5.0	0.0			B381954	27.43	28.96	0.032			VA05058633	1.53
							chl	3																					
0																						B381955	28.96	29.14	0.039			VA05058633	0.18
																						B381956	BLANK		<0.005			VA05058633	
2	1	0.5	1.0			100	chl/s	3	0	5								5.0				B381957	29.14	30.50	0.034			VA05058633	1.36
0																						B381958	30.50	30.60	0.029			VA05058633	0.10
2	6	0.5	0.7	60		5	chl/s	4,5	0	100								5.0				B381959	30.60	32.00	0.160			VA05058633	1.40
0																						B381960	32.00	32.30	0.193			VA05058633	0.30
1	6	0.4	0.4	20		10	chl/s	1,4	0	100								5.0				B381961	32.30	33.53	0.025			VA05060235	1.23
2	2	0.5	1.0	40		1	k/chl	2,1		100								5.0											
							s	4	0																					
1	6	0.4	0.4	20		10	chl/s	1,4	0	100								5.0				B381962	32.30	33.53	0.015	DUP		VA05060235	
2	2	0.5	1.0	40		1	k/chl	2,1		100								5.0											
0																						B381963	33.53	34.00	0.038			VA05060235	0.47

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 3 of 16		
DRILL HOLE # : DG05-290C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		34.00	37.20	Alt'd GND; less sericite, chl & clay; more silicified; appears heated to aphanitic texture w/ oxidized sulphides. Overall color is dark brownish grey. Vnlets all rearranged, convoluted directions, lim. Dark grey sand makes up 5% of first sample (appears as first 5cm of section, little bit under core in box).	3	1	0	1	0	
10		37.20	39.88	Minor alt'd GND w/ small sulphide vns at random orientations, bent and sheared. Mostly ox'd sulphides in vns w/ milky qtz & feldspar (k-spar).	1	1	1	0	0	
10		39.88	43.35	Minor alt'n grading to mod alt'd GND, mostly chloritization. GND texture preserved and core remains relatively competent. Slickensides on vn faces shown in k-spar & ox'd py.	1	1	3	0	0	
10		43.35	52.54	Sericitized & chloritized, soft GND. Alt'n is pervasive so rock is crumbly: pale greenish grey to white. ~2 sulphide vns per metre on frac faces, usually at 20-30° to CA. Ox'd py and ser form slickensides, vns rearranged to random orientations.	0	4	3	3	0	
10		52.54	57.74	Original GND texture reappears and selvages are more clearly visible around vns. Rock is less sheared as well; less movement indicated in vns.	0	3	2	2	1	
10		57.74	59.07	Highly alt'd GND; wide selvages around sulphide and sulphide/qtz vns make rock crumbly, especially at vns. Minor slickensides on these faces.	1	4	3	2	0	
10		59.07	65.40	Highly-mod alt'd GND. Orig texture preserved btwn vns' selvages. 75% alt'd, v. broken up & crumbly. Slickensides appear @ 63.5m, none previous.	0	3	2	1	1	
10		65.40	66.17	Three large sulphide vns (3cm, 1cm, & 1cm wide) surrounded by extremely alt'd but competent core. GND texture completely erased.	1	4	3	2	2	
10		66.17	73.68	Mod alt'd GND. Orig texture preserved btwn vns' selvages. More competent and recovery is good (>80%). From 66.17m-67.06m: core is striped w/ bands of silicified old qtz vns. V. minor (<2%) ox'd py associated, not used in vn count. Vnlets of carb shift sulphide vns dextrally if sulph vn is to 60°.	0	3	2	1	1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	6	0.8	2.0	50	25	2	k/chl	2,1		100								5.0				B381964	34.00	35.05	0.538			VA05060235	1.05
							s	3																					
4	6	0.5	2.0	10		0.5	chl/s	2,3		95		5.0						2.0				B381965	35.05	35.65	0.227			VA05060235	0.60
2	6	1.0	2.0	70	10	1	k/s	3	2	60					40.0			5.0				B381966	35.65	36.45	0.104			VA05060235	0.80
5	6	1.0	2.2	35	25	1	k/s	3,1	2	60		20.0			20.0			2.0				B381967	36.45	37.20	0.474			VA05060235	0.75
4	6	0.5	2.0	10	45	2	k/s	1	0	60					40.0			3.0				B381968	37.20	38.10	0.124			VA05060235	0.90
4	6	0.5	2.0	10	45	2	k/s	1	0	60					40.0			3.0				B381969	37.20	38.10	0.114	PD/CA		VA05060235	0.90
																						B381970	STANDARD 7G		4.530	7G		VA05060235	
8	6	0.5	4.0	25	65	0.5	k/q	1,2	3	60					40.0			4.0				B381971	38.10	39.62	0.183			VA05060235	1.52
2	6	1.5	2.5	20		1	k/q	3,1	3	40	5.0		5.0		30.0			4.0				B381972	39.62	39.88	0.364			VA05058633	0.26
2	2	0.5	1.0	10		1	k	2	0													B381973	39.88	41.15	0.018			VA05058633	1.27
1	1	0.5		60		0.4	q	1	0				0.1																
3	6	0.5	1.0	20		1	q/k	2	0	40								5.0				B381974	41.15	42.67	0.014			VA05058633	1.52
1	2	0.5	0.5	20		1	q	2	0	10								5.0											
3	6	1.0	2.0	15		1	q/s	2,1	0	70								3.0				B381975	42.67	43.35	0.082			VA05058633	0.68
							k	2														B381976	BLANK		<0.005			VA05058633	
3	6	0.2	0.6	10	90		s/chl	4,3	0	100								4.0				B381977	43.35	44.20	0.048			VA05060235	0.85
2	6	0.2	0.4	25	65		s/chl	4,2	0	100								4.0				B381978	44.20	45.72	0.065			VA05060235	1.52
2	6	0.3	0.5	30	75		s/chl	4,2	0	60			40.0					4.0	0.0			B381979	45.72	47.24	0.025			VA05060235	1.52
	6	0.4	1.0	35	20		s/chl	4,1	0	60			40.0					4.0				B381980	47.24	48.77	0.137			VA05060235	1.53
6	6	0.6	2.0	40	20		q/s	2,4	0	70			30.0					3.0				B381981	48.77	50.29	0.280			VA05060235	1.52
6	6	0.6	2.0	40	20		q/s	2,4	0	70			30.0					3.0				B381982	48.77	50.29	0.160	DUP		VA05060235	1.52
4	6	0.5	1.2	60	55		s/chl	4,1	0	90			10.0					2.0				B381983	50.29	51.82	0.175			VA05060235	1.53
2	6	0.6	1.0	35	10		s	4	0	100								4.0				B381984	51.82	52.54	0.045			VA05060235	0.72
3	1	0.5	1.2	25	50	1.5	q/s	2,4	0				20.0									B381985	52.54	53.34	0.027		vns radiating	VA05060235	0.80
3	4	0.3	0.9	75		10	cb/chl	2,3																					
3	6	0.5	1.1	45	60	20	q/s	3	0	20			50.0					4.0				B381986	53.34	54.86	0.047			VA05060235	1.52
4	6	2.0	2.6	30	60	20	q/s	3,2	1	50			40.0					2.0				B381987	54.86	56.35	0.175			VA05060235	1.49
							s/chl	4,1																					
5	6	1.0	2.0	40	70	10	q/cb	2,1	1	50			10.0					4.0				B381988	56.35	57.74	0.097			VA05058633	1.39
5	6	1.0	2.0	40	70	10	q/cb	2,1	1	50			10.0					4.0				B381989	56.35	57.74	0.104	PD/CA		VA05058633	1.39
																						B381990	STANDARD 2B		3.230	2B		VA05058633	
4	6	1.0	1.6	25		20	q/chl	3,1	0	30			40.0					3.0				B381991	57.74	59.07	0.132			VA05058633	1.33
							s	3																					
1	6	0.5	0.5	25		3	q/s	3	0				40.0						2.0			B381992	59.07	59.44	0.235			VA05058633	0.37
5	6	0.2	1.0	35		1	q/cb	3,1	0	10			40.0					4.0				B381993	59.44	60.96	0.048			VA05058633	1.52
10	1	0.2	2.0	35	75	1	s/chl	3,2	0	15								4.0											
4	6	0.5	1.2	35		2	q/cb	3,1	0	40			20.0					4.0				B381994	60.96	62.48	0.201			VA05060235	1.52
10	1	0.2	2.0	35	75	2	q/chl	4,2		15								4.0											
2	1	0.3	0.6	70		1	q/cb	4,2		3								0.0				B381995	62.48	64.01	0.035			VA05060235	1.53
3	6	0.2	0.6	50	60	10	q/s	2,4	0	40			40.0					4.0				B381996	BLANK		<0.005			VA05060235	
							chl/cb	3,2																					
8	6	0.3	1.6	35	60	10	q/s	2,4		20			60.0					2.0				B381997	64.01	65.40	0.070			VA05060235	1.39
							chl/cb	3,2																					
3	6	3.0	5.0	35		27	s/chl	4,3	2	80			20.0					3.0				B381998	65.40	66.17	0.683			VA05060235	0.77
							q/cb	2																					
1	6	0.3	0.3	40		5	s/q	4,3	2	85								4.0				B381999	66.17	67.06	0.023			VA05060235	0.89
5	6	0.6	1.6	60	45	5	q/s	1,4	0	30			40.0					4.0				B382000	67.06	68.58	0.062			VA05060235	1.52
2	6	0.5	1.0	70		40	q/s	3,2	2	30			15.0					3.0				B382001	68.58	68.96	0.151			VA05060235	0.38
							chl	3																					
2	6	0.5	1.0	70		40	q/s	3,2	2	30			15.0					3.0				B382002	68.58	68.96	0.118	DUP		VA05060235	

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 5 of 16		
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		73.68	74.68	Extreme alt'n surrounds 5 sulphide vns, no orig GND texture, all alt'd out.	0	4	3	3	2	
10		74.68	77.72	Carbonate veinlets throughout section, approx 5 per 10cm interval. Highly alt'd section. Only relict qtz and bt remnants of GND texture. Overall colour greenish white to pale grey.	0	4	1	2	2	
10		77.72	80.22	Carbonate pervasive in 20cm and 50cm lengths, separated by 25cm of moderately alt'd GND (minor cb, chl, and silicified) around sulphide vein. From 79.25 to 80.22m, rock is this mod alt'd coherent core.	1	3	2	2	3	
10		80.22	82.00	Extremely alt'd GND. Sericite and carbonate pervasive. Entire section is too crumbly to remove from box in core form. 1-2mm bt grains evenly distributed are the only remaining GND texture. Veins no longer visible. Few wisps of sulphides and linear crumbles of carbonate but nothing definitive.	2	5	3	3	4	
10		82.00	85.62	Mod alt'd GND. Texture preserved through predominantly carb-alt'd rock. Veinlets randomly oriented and pervasive through matrix of GND. Po appears as subhedral grains within qtz/carb veins with grey qtz (max. 0.5cm) within milky qtz/carb selvage.	0	1	1	0	3	
10		85.62	91.44	Zone of high alt'n. Carb + chl + ser pervasive so rock is soft and crumbly. Overall colour is greenish pale grey. Sulphide veins at 86.15m (1cm) and at 89.4m (0.5cm).	0	3	3	0	3	
10		91.44	91.94	Selvage and vein sample. Vein is grey qtz with ~20% sulphides (ox'd py and aspy). Selvage shows high alt'n. Sulphides concentrated in centre of vein in 1cm wide section. Few 1-2mm lenses w/in qtz vein as well.	0	3	3	1	3	
10		91.94	95.19	Low to mod alt'n. GND texture preserved between carbonate veinlets and qtz/carb veins, which have chloritized selvages.	0	1	2	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

PAGE 6 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	6	0.3	1.2	60	60	2	q/s	3	1	20			60.0					5.0				B382003	68.96	70.10	0.131			VA05060235	1.14
							chl/cb	1,2																					
5	1	0.5	2.5	70	35	2	q/s	3	0	10			20.0					2.0	0.0			B382004	70.10	71.63	0.076		slickenside s assc'd w/ carb	VA05060235	1.53
2	4	0.5	1.0	30		4	cb/s	4,3	0	30								4.0											
3	4	0.6	1.5	20	10	5	q/cb	3,2	3	5								5.0				B382005	71.63	73.15	0.107			VA05060235	1.52
3	1	0.6	1.5	50	80	1	q/cb	3	0				30.0																
1	6	1.5	1.5	80		20	q/cb	3,1	1	60			10.0					4.0											
							s	3	0																				
1	4	0.5	0.5	10		2	cb/s	2	1				2.0						4.0			B382006	73.15	73.68	0.059			VA05060235	0.53
							chl	2																					
5	6	0.8	1.6	35		4	cb/q	3,2	0	60			40.0					5.0	0.0			B382007	73.68	74.68	0.088		slickenside s in aspy	VA05060235	1.00
2	1	1.5	2.0	70		0.5	q	3	0				15.0									B382008	74.68	76.20	0.062			VA05060235	1.52
2	1	1.5	2.0	70		0.5	q	3	0				15.0									B382009	74.68	76.20	0.061	PD/CA		VA05060235	1.52
																						B382010	STANDARD 6F		2.820	6F		VA05060235	
2	4	0.5	1.0	20		0.5	cb/q	3,1	0	5								5.0				B382011	76.20	77.72	0.039			VA05060235	1.52
3	1	0.8	1.8	35	50	1	q/chl	3,1					20.0																
2	1	0.6	1.2	40		15	q/chl	2,3	0				20.0					5.0				B382012	77.72	79.25	0.048			VA05060235	1.53
4	4	2.0	6.0	50	150	50	cb/chl	5,2	0	5								5.0											
1	6	0.5	0.5	40		15	q/chl	2,4	0	80								2.0											
							cb	3																					
1	6	0.5	0.5	30		4	cb/q	1,2	0	60								4.0				B382013	79.25	80.22	0.025			VA05058633	0.97
0																						B382014	80.22	81.24	0.048			VA05058633	1.02
0																						B382015	81.24	82.00	0.103			VA05058633	0.76
																						B382016	BLANK		<0.005			VA05058633	
2	4	0.5	1.0	70	45	4	cb	4	1	5								5.0				B382017	82.00	82.62	0.037			VA05058633	0.62
6	3	0.2	1.2	65		1	q/cb	3	0						3.0			2.0				B382018	82.62	83.82	0.027		grey qtz w/in milky qtz	VA05060235	1.20
2	4	0.3	0.6	45		1	cb/chl	3	0																				
8	3	0.5	3.0	65		2	q/cb	3	0		5.0											B382019	83.82	85.34	0.047			VA05060235	1.52
2	3	0.4	0.8	70		1.5	q/cb	3	0		3.0											B382020	85.34	85.62	0.021			VA05060235	0.28
1	8	3.0	3.0	35		30	cb	4	2	20			10.0					5.0	0.0			B382021	85.62	86.87	0.196			VA05060235	1.25
1	3	10.0	10.0	50		20	cb/q	3,2	0				20.0	10.0															
							chl	2																					
1	3	10.0	10.0	50		20	cb/q	3,2	0				20.0	10.0								B382022	85.62	86.87	0.468	DUP		VA05058633	1.25
3	3	0.3	0.9	65		1	q/cb	3	0													B382023	86.87	88.39	0.050			VA05058633	1.52
							chl	1																					
3	6	0.5	1.5	45		20	q/chl	2		10			15.0					5.0	1.0										
							s/cb	3																					
2	1	1.2	1.8	55	45	2	q/chl	3	0				20.0						2.0			B382024	88.39	89.92	0.103			VA05058633	1.53
1	3	0.5	0.5	55		0																							
4	1	0.5	1.2	35	155	4	q/chl	4	0				20.0						1.0			B382025	89.92	91.44	0.072			VA05058633	1.52
							cb/s	1																					
1	6	0.5	0.5	50		0.5	q/cb	2		60			10.0					5.0											
1	1	10.0	10.0	50		40	chl/cb	3		20			10.0					4.0				B382026	91.44	91.94	0.209			VA05060235	0.50
							q/s	1,3																					
2	3	1.0	2.0	50		3	q/chl	3					15.0						1.0			B382027	91.94	92.96	0.083			VA05060235	1.02
							cb/s	2																					
3	3	0.5	1.5	50		2	q/chl	3	0		8.0		5.0						1.0			B382028	92.96	94.49	0.053			VA05060235	1.53
							cb	2																					
3	3	0.5	1.5	50		2	q/chl	3	0		8.0		5.0						1.0			B382029	92.96	94.49	0.052	PD/CA		VA05060235	1.53

DRILL LOG LEGEND - P1

DATE: July 4-8, 2005 PAGE 7 of 16

DRILL HOLE # : DG05-290C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		95.19	96.72	Mod to highly alt'd GND. Chl+carb alt'n pervasive, plus silicification makes texture grade to cryptocrystalline but GND texture still visible in 10% of sample.	0	2	3	0	3	
10		96.72	97.83	Highly alt'd GND. Carb+chl+ser alt'n pervasive such that rock is easily broken, but coherent. 10% preservation of GND texture.	0	4	4	2	4	
10		97.83	101.92	Highly alt'd GND. Carb/chl/ser alt'n pervasive. Rock is highly broken and crumbly, as alt'n is throughout matrix.	0	4	4	3	4	
10		101.92	102.66	Unalt'd GND w/ qtz veins w/ very few sulphides and small selvages	0	1	1	0	0	
10		102.66	111.25	Carb-infused GND. Crumbling to coarse sand texture w/ no longer than 15cm lengths of competent rock. Recovery is good (65-70%), but quality so poor, veins are not readily visible; count is probably low. Disseminated aspy throughout GND.	0	1	1	2	4	
10		111.25	115.26	More competent GND. 60% competent rock sulphide/carb veins may have started as only sulph veins; carb secondary. Crumbly section abuts competent at 17° to CA.	0	1	1	1	2	
10		115.26	119.78	90% competent GND. Crumbly carb-infused sections (1-12cm wide) make up 10% of section and intersect at 25° to 40° with sharp boundaries. Sample from 115.82 to 116.71m contains one crumbly section with sulph vein adjacent to 25cm long section of 'bleached'/carbonitic GND w/ texture preserved. Colour is orange-green beige. (orange=siderite (ox'd carb), green = chl). From 117.35 to 118.15m, another alt'd section (2 samples). There are at least 2 generations of qtz veining here, plus the carb. Latest qtz episode is most visible, so these veins are noted. Aspy throughout width of vein (not selvage).	0	1	1	1	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ec = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B382030	STANDARD 6F		2.730	6F		VA05060235	
4	3	1.0	2.0	50		4	q/chl	3	0		4.0		20.0									B382031	94.49	95.19	0.090			VA05060235	0.70
							cb/s	2																					
5	6	1.5	4.0	40	70	20	q/cb	1,4	0	40			10.0					3.0				B382032	95.19	96.20	0.115			VA05060235	1.01
							chl/s	3																					
4	1	0.8	3.2	65	45	4	q/chl	3					30.0									B382033	96.20	96.72	0.058			VA05060235	0.52
							cb	3																					
1	1	0.5	0.5	60		6	q/chl	3		10			3.0					4.0	1.0			B382034	96.72	97.83	0.045			VA05060235	1.11
							cb/s	3																					
3	6	1.0	1.4	55		5	q/cb	4		50								5.0											
							chl/s	2																					
6	1	1.0	5.0	60	30	5	q/chl	3		15			10.0					3.0				B382035	97.83	99.06	0.082			VA05060235	1.23
							cb/s	4																					
																						B382036	BLANK		<0.005			VA05060235	
1	6	6.0	6.0	30		30	cb/s	4		60	2.0		5.0					4.0				B382037	99.06	99.60	0.496			VA05060235	0.54
							chl	4																					
10	1	1.0	6.0	30	60	3	q/cb	4					10.0						2.0			B382038	99.60	100.58	0.153			VA05060235	0.98
							chl/s	2																					
3	1	0.5	1.5	30	60	15	chl/cb	4					15.0						3.0			B382039	100.58	101.92	0.082			VA05060235	1.34
							q/s	2																					
3	3	1.0	2.5	90	40	1	q/cb	3					3.0									B382040	101.92	102.66	0.024			VA05060235	0.74
							chl	3																					
2	3	0.5	1.0	30		2	cb/s	4	0													B382041	102.66	103.63	0.035			VA05060235	0.97
							chl/q	3																					
2	3	0.5	1.0	30		2	cb/s	4	0													B382042	102.66	103.63	0.027	DUP		VA05060235	0.97
2	3	1.0	2.0	50		10	chl/cb	1,4	1	5								5.0				B382043	103.63	105.16	0.022			VA05060235	1.53
7	3	0.5	3.5	35		4	q/chl	4					10.0						2.0			B382044	105.16	106.68	0.072			VA05060235	1.52
							cb	2																					
7	1	0.3	2.1	45		2	q/cb	3,2			2.0		15.0									B382045	106.68	108.20	0.058			VA05060235	1.52
							chl	1																					
8	1	0.5	3.5	10	45	2	q/cb	3					20.0						3.0			B382046	108.20	109.73	0.051			VA05058633	1.53
							chl	1																					
4	1	1.0	4.0	65		3	q/chl	3					30.0					2.0				B382047	109.73	111.25	0.105			VA05058633	1.52
							cb	3																					
3	4	0.3	0.9	30	50	2	cb/s	3,2																					
2	1	0.5	1.0	50		2	q/cb	.					15.0									B382048	111.25	112.78	0.430			VA05058633	1.53
8	3	0.5	4.0	50		1	q/cb	2,3					40.0						1.0										
							chl	2																					
8	3	0.5	4.0	50		1	q/cb	2,3					40.0						1.0			B382049	111.25	112.78	0.076	PD/CA		VA05058633	1.53
																						B382050	STANDARD 1A		0.887	1A		VA05058633	
5	1	1.0	3.0	50	30	6	q/cb	3					60.0									B382051	112.78	114.30	0.166			VA05060235	1.52
							chl	3																					
4	1	0.5	2.0	50	30	2	q/cb	3					50.0									B382052	114.30	115.26	0.183			VA05060235	0.96
							chl	1																					
7	1	2.0	4.0	30	40	4	q/chl	3					40.0									B382053	115.26	115.82	0.376			VA05060235	0.56
1	8	2.0	2.0	40		10	cb/s	5	1	20								5.0				B382054	115.82	116.71	0.240			VA05060235	0.89
8	1	5.0	8.5	40	55	4	q/cb	2,3		10			20.0					5.0											
							chl	1														B382055	116.71	117.35	0.141			VA05060235	0.64
7	1	0.8	2.8	35		12	q/chl	2,4	0				20.0																
							cb	3														B382056	BLANK		<0.005			VA05060235	

DRILL LOG LEGEND P1	DATE: July 4-8, 2005	PAGE 9 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		119.78	121.92	Fewer qtz veins continue into silicified GND. Colour is med grey, texture cryptocrystalline except speckles of 1mm bt. Rock readily breaks on randomly oriented veinlets of carbonate.	0	0	1	0	1	
10		121.92	124.97	Silicified GND infused with carb; rock is soft and crumbly. Veinlets of calcite generally run at 45° to CA, so breakage is predominantly on this angle as well. 20% soft carb-clay. Slickensides in carb veins.	0	1	1	1	3	
10		124.97	129.54	Back to less-carbonitized, silicified GND (as 119.78-121.92m), veinlets of carb at lower angle	0	0	1	0	1	
10		129.54	131.71	Gradation back to unsilicified GND. Qtz veins w/ carb/chl selvages more prominent. Aspy is 1-2mm, w/in qtz veins, not ox'd or alt'd. From 131.06 to 131.71m, 2 qtz veins and 2 sulph veins account for entire sample's alt'n (65cm chl'd and cb'd to yellowish green)	0	0	3	1	2	
10		131.71	134.56	Carb-infused cryptocrystalline, silicified GND w/ numerous qtz veins. 50% carb-clay crumbles. Sulphide 'veins' attached to edges of carb veins and/or qtz veins.	0	1	2	3	3	
10		134.56	135.39	Unalt'd GND (not silicified), w/ 20% carb-clay crumbles.	0	0	1	1	1	
10		135.39	137.80	Silicified cryptocrystalline GND w/ qtz veins with large chl'd selvages. Carb veinlets in random orientations - web appearance - cause breakage of otherwise competent core. (<5% clay). Good potential for gold here. <1mm flecks seen	0	0	1	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval					
						Selvages				Sulphides										Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
3	1	0.4	1.2	50		55	q/chl	2,4	1	25								4.0				B382057	117.35	117.90	0.139		following two samples are one selvage, total 80cm	VA05060235	0.55
							cb	3																					
2	6	1.2	20.0	60						100								4.0											
1	4	1.2	1.2	30		25	q/chl	2,4	1													B382058	117.90	118.15	0.241			VA05060235	0.25
2	8	4.0	7.0	30			cb	3																					
4	1	2.0	6.0	30	50	3	q/chl	4	0				20.0						1.0			B382059	118.15	118.87	0.114			VA05060235	0.72
							cb	1																					
11	1	3.0	8.5	50	70	15	q/chl	4	0				1.0									B382060	118.87	119.78	0.181			VA05060235	0.91
							cb	1																					
4	1	0.5	2.0	35	20	4	q/chl	3	0				10.0									B382061	119.78	120.40	0.027			VA05060235	0.62
							cb	1																					
4	1	0.5	2.0	35	20	4	q/chl	3	0				10.0									B382062	119.78	120.40	0.019	DUP		VA05060235	0.62
1	1	0.4	0.4	35		1	chl/cb	1					5.0					1.0				B382063	120.40	121.92	0.053			VA05058633	1.52
							q	3																					
3	1	0.4	1.2	150		5	q/chl	3,2					20.0					2.0				B382064	121.92	123.44	0.079			VA05058633	1.52
4	4	0.3	1.2	50	10	0.4	cb	3														B382065	123.44	124.97	0.095			VA05058633	1.53
7	4	1.0	2.2	40		0.5	cb/s	3,1																					
?	1	0.3	0.6	25		1.5	q/chl	3					15.0																
							cb	2																					
3	4	0.3	0.9	25		1.5	cb	2														B382066	124.97	126.49	0.039			VA05058633	1.52
5	1	1.0	3.0	40	25	4	q/chl	4	0				15.0									B382067	126.49	128.02	0.041			VA05058633	1.53
							cb	2																					
6	1	1.5	2.5	40	45	5	q/chl	4					15.0									B382068	128.02	129.54	0.136			VA05058633	1.52
							cb	2																					
6	1	1.5	2.5	40	45	5	q/chl	4					15.0									B382069	128.02	129.54	0.191	PD/CA		VA05058633	1.52
																						B382070	STANDARD 5E		1.440	5E		VA05058633	
7	1	1.0	4.5	35	30	8	q/chl	4					15.0									B382071	129.54	130.28	0.099			VA05058633	0.74
							cb	3																					
7	1	0.5	3.5	30	25	4	q/chl	4					15.0									B382072	130.28	131.06	0.282			VA05058633	0.78
							cb	3																					
2	1	0.5	1.0	40		25	q/chl	4					5.0									B382073	131.06	131.71	0.205			VA05058633	0.65
							cb	3																					
2	6	0.6	0.9	40		40	q/chl	4		20			30.0					4.0											
							cb	4																					
6	1	1.0	3.5	50	30	6	q/chl	4					15.0					2.0				B382074	131.71	132.83	0.097			VA05058633	1.12
							cb/s	3,1																					
3	3	2.0	4.0	170		0							3.0																
3	1	1.0	3.0	40	4		q/chl	4					10.0					3.0											
							cb/s	1																					
3	3	1.0	2.0	150	0																	B382075	132.83	134.11	0.053			VA05058633	1.28
																						B382076	BLANK		<0.005			VA05060567	
2	6	0.5	1.0	150	170	8	cb	5	0	80								5.0				B382077	134.11	134.56	0.130		sulph. appears as black clay (ox'd py (?))	VA05060567	0.45
							chl/s	1																					
5	1	1.0	4.0	40		2	q/chl	3					10.0									B382078	134.56	135.39	0.040			VA05060567	0.83
							cb	1																					
2	4	1.5	2.0	30		1	cb	3																					
3	1	0.7	1.3	35	50	4	q/chl	4					5.0									B382079	135.39	136.40	0.021			VA05060567	1.01
							cb	3																					

DRILL LOG LEGEND - P1	DATE: July 4-8, 2005	PAGE 11 of 16	
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		137.80	139.08	Section v. broken up. Influx of carb.	0	0	1	2	3	
10		139.08	141.62	Unalt'd GND w/ qtz veins with carb/chl'd selvages. Solid rock.	0	0	1	0	1	
10		141.62	144.78	50% unalt'd GND w/ qtz veins, 50% highly alt'd around carb-infused sections, at 60° to CA. Carb'd sections are crumbly at centre (max 20cm) with competent, yellow-white surrounding selvages (up to 10cm on either side). Slickensides in sulphides (aspy and py) at margins of qtz/carb/sulph veins	0	1	1	1	2	
10		144.78	146.21	Zone of extreme alt'n. GND texture barely visible beneath carb/chl alt'n, causing rock to be soft but still competent. Lenses of sulphides on carb veins show moderate slickensides	0	2	4	2	4	
10		146.21	153.53	Qtz veins with selvages continue into zone of greater carb alt'n in veinlets and through matrix of ~40% of section, causing crumbly/competent alternating sections approx 20cm long, ave. Late carb veins overprint old qtz veins and incorporate sulphides (from qtz to carb vein). Veins are at 120° to each other.	0	1	2	2	2	
10		153.53	161.24	Carb-infused GND. Competent sections <15cm long. Carb veining is wider than before: approx. 5-10% of sample is pure calcite!	0	1	2	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	1.0	3.0	40	25	6	q/chl	4		20			5.0									B382080	136.40	137.16	0.026			VA05060235	0.76
							cb	2																					
7	1	1.2	4.2	40		5	q/chl	4	0	10			15.0									B382081	137.16	137.80	0.198			VA05060235	0.64
							cb	2																					
7	1	1.2	4.2	40		5	q/chl	4	0	10			15.0									B382082	137.16	137.80	0.072	DUP		VA05060235	0.64
8	1	0.5	2.0	40	50	3	q/chl	4					15.0									B382083	137.80	138.68	0.098			VA05060235	0.88
							cb	2																					
2	4	0.5	1.0	70		0.4	cb	4																					
4	4	0.5	2.0	25		4	cb	4														B382084	138.68	139.08	0.014			VA05060235	0.40
6	1	0.5	3.0	40	160	2	q/chl	3,1			3.0		5.0						2.0			B382085	139.08	140.21	0.047			VA05058633	1.13
6	3	1.0	4.0	30		2	q/cb	3		30																			
							chl	3																					
4	1	1.0	4.0	35	50	4	q/cb	3					20.0									B382086	140.21	141.09	0.131			VA05058633	0.88
							chl	3																					
4	3	1.0	4.0	60		6	q/cb	3		5			10.0					2.0				B382087	141.09	141.62	0.025			VA05058633	0.53
							chl	2																					
1	3	20.0	20.0	45		20	q/cb	4					15.0					2.0				B382088	141.62	142.25	0.502			VA05058633	0.63
							chl	1																					
1	3	20.0	20.0	45		20	q/cb	4					15.0					2.0				B382089	141.62	142.25	0.012	PD/CA		VA05060235	0.63
																						B382090	STANDARD 7G		4.390	7G		VA05060235	
3	1	2.0	5.0	30	75	4	q/chl	3					10.0						1.0			B382091	142.25	143.26	0.206			VA05060235	1.01
	6	1.0	1.6	40		20	q/chl	3	1	40			20.0					4.0											
							cb	3																					
1	6	0.6	0.6	20		0.4	q	2	0				70.0																
5	4	0.3	0.9	45		10	cb	3														B382092	143.26	144.78	0.060			VA05060235	1.52
5	1	2.5	4.4	30		8	q/chl	3					15.0																
							cb	1																					
2	1	1.5	2.5	40	50	6	q/chl	2					15.0									B382093	144.78	146.21	0.046			VA05060235	1.43
							cb	3																					
2	3	1.8	3.0	45		10	cb	4		10								5.0											
							q/chl	3																					
2	1	1.0	1.5	65		1	q/chl	3					10.0									B382094	146.21	146.95	0.034			VA05060235	0.74
3	1	1.0	3.0	30	50	3	q/chl	3					5.0						2.0			B382095	146.95	147.83	0.030			VA05060235	0.88
3	3	2.0	5.0	50		1	cb	2														B382096	BLANK		<0.005			VA05060235	
3	1	1.0	1.6	60		8	q/chl	4	1	10			10.0					5.0				B382097	147.83	148.65	0.054		slickens in sulphides	VA05060235	0.82
							cb	3																					
6	1	1.0	3.0	30	120	1	q/chl	3					30.0									B382098	148.65	149.35	0.121		veins not visible; only crumbly selvage	VA05060235	0.70
2	4			45		12	cb	4																					
6	1	0.5	3.0	40	50	1	q/cb	4					20.0					1.0				B382099	149.35	150.88	0.072			VA05060237	1.53
							chl	1																					
2	4	0.5	1.0	50	140	1	cb	3																					
4	1	3.0	5.2	60	20	8	cb/chl	4					10.0									B382100	150.88	152.40	0.061			VA05060237	1.52
							q	3																					
1	6	0.7	0.7	70		3	q/chl	4,1																					
4	1	0.5	1.4	30	60	1	q/chl	4,1					10.0						2.0			B382101	152.40	153.53	0.018			VA05060237	1.13
3	4	0.5	1.5	150		2.5	cb	3																					
4	1	0.5	1.4	30	60	1	q/chl	4,1					10.0						2.0			B382102	152.40	153.53	0.020	DUP		VA05060237	1.13
1	1	0.5	0.5	40		1	q/chl	3,2					2.0						4.0			B382103	153.53	153.92	0.013			VA05060237	0.39
9	1	0.5	4.5	60	20	6	q/chl	3,1			5.0											B382104	153.92	155.45	0.028			VA05060237	1.53
7	1	0.5	3.5	50	130																	B382105	155.45	156.97	0.028			VA05060237	1.52

DRILL LOG LEGEND P1

DRILL HOLE # : DG05-290C

DATE: July 4-8, 2005 PAGE 13 of 16

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.24	161.99	GND is competent but highly alt'd with carb and chl, and is silicified around 6 sulphide-rich veins. On broken face more old qtz veins are visible but highly silicified. Mod slickensides on sulph-vein face.	1	0	3	0	4	
10		161.99	163.67	Relatively unalt'd section; carb influx, sections crumbly	0	1	2	2	3	
10		163.67	166.12	Highly to extremely alt'd GND. Carbonate pervasive across competent and incompetent ("carb-clay-crumble") sections. 60% crumbly.	1	1	3	3	4	
10		166.12	167.61	Selvage and 15cm sulphide vein. Upper selvage is more carbonitized (crumbly), than lower selvage (competent). Lower selvage contains 2 qtz veins (may help to explain less carb down there).	1	1	3	1	3	
10		167.61	168.82	Numerous grey-milky qtz veins w/ lots of aspy (2 samples)	1	1	3	0	2	
10		168.82	175.26	Moderately silicified GND with ~30cm sections of carb-infused, crumbly rock. Qtz veins visible in competent sections and as linear relicts qtz pebbles. ~50% of section is broken up, crumbly rock.	1	2	3	1	3	
10		175.26	181.36	Highly to extremely alt'd GND silicified plus chl/cb selvage alt'n around sheeted qtz veins and sulphides. Slickensides seen on sulph vein faces, in ox'd py and ser and calcite.	1	2	3	1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.0	2.5	20	40	4	q/chl	2			5.0		15.0									B382106	156.97	157.55	**0.095**			VA05060237	0.58
							cb	2																					
1	1	1.5	1.5	50		25	cb	5		25			5.0					4.0				B382107	157.55	158.96	**0.071**		mod. slickens on sulph vein	VA05060237	1.41
1	6	0.8	0.8	140		8	q/cb	3,4		65			10.0					4.0											
4	1	1.0	3.0	35		2	q	4					10.0									B382108	158.96	160.02	**0.100**			VA05060237	1.06
4	4	1.0	4.0	25		6	cb	4														B382109	158.96	160.02	**0.108**	PD/CA		VA05060237	1.06
4	4	1.0	4.0	25		6	cb	4														B382110	STANDARD 1A		**0.979**	1A		VA05060237	
																						B382111	160.02	161.24	**0.029**			VA05060237	1.22
5	3	1.0	3.0	60	30	5	q/cb	4	1				5.0									B382112	161.24	161.99	**0.249**			VA05060237	0.75
3	6	0.5	0.8	60	40	4	q/cb	4	1	90								4.0				B382113	161.99	163.07	**0.032**			VA05060237	1.08
4	1	1.0	3.5	50	70	2	q/cb	3	1				5.0									B382114	163.07	163.67	**0.045**			VA05060237	0.60
6	1	0.7	3.2	65	40	3	q/cb	3	1				10.0						3.0										
2	4	0.3	0.6	150		0																B382115	163.67	164.59	**0.262**			VA05060237	0.92
5	6	0.5	2.4	40	60	10	q/cb	4		50			15.0	5.0				4.0											
							chl/s	3,1														B382116	BLANK		**<0.005**			VA05058634	
2	1	1.0	2.0	65		15	q/cb	2,4	0				5.0									B382117	164.59	165.06	**0.125**			VA05058634	0.47
							chl	2																					
1	3	1.0	1.0	145		0							5.0						4.0										
4	1	1.0	4.0	80	70	2	q/chl	3	0				8.0						1.0			B382118	165.06	166.12	**0.044**			VA05058634	1.06
1	6	15.0	15.0	35		137	q/chl	4,3		75	2.0	10.0				1.0		2.0				B382119	166.12	167.61	**4.850**			VA05058634	1.49
							cb/s	3,1																					
2	1	0.6	1.0	60	70	0																							
6	1	1.0	5.0	35		20	q/chl	4,3	1	5			30.0						1.0			B382120	167.61	168.23	**0.290**			VA05058634	0.62
							cb	1																					
5	1	1.0	3.0	50	30	10	chl/cb	3	1				15.0						1.0			B382121	168.23	168.82	**0.024**			VA05058634	0.59
							q	3																					
5	1	1.0	3.0	50	30	10	chl/cb	3	1				15.0						1.0			B382122	168.23	168.82	**0.019**	DUP		VA05058634	0.59
2	1	0.5	1.0	25	70	1	q	3					25.0									B382123	168.82	169.16	**0.024**			VA05058634	0.34
9	1	2.0	11.0	50	20	3	q/chl	4,2					10.0						2.0			B382124	169.16	170.49	**0.035**			VA05058634	1.33
							cb	3																					
7	1	1.0	5.0	30	60	4	q/chl	4,2					10.0						1.0			B382125	170.49	171.51	**0.021**			VA05060237	1.02
							cb	3																					
6	1	0.5	2.0	40		4	q/chl	3			2.0		10.0									B382126	171.51	172.68	**0.018**			VA05060237	1.17
							cb	3																					
4	1	1.0	2.6	45		20	q/chl	3					5.0									B382127	172.68	173.74	**0.125**			VA05060237	1.06
							cb	3																					
1	6	0.3	0.3	40						5	5.0		40.0					5.0											
8	1	1.0	3.5	40	50	1	cb/q	3					5.0									B382128	173.74	175.26	**0.028**			VA05060237	1.52
8	1	1.0	3.5	40	50	1	cb/q	3					5.0									B382129	173.74	175.26	**0.028**	PD/CA		VA05060237	1.52
																						B382130	STANDARD 4D		**0.435**	4D		VA05060237	
7	1	1.2	5.0	40		4	q/chl	3					10.0						3.0			B382131	175.26	176.16	**0.128**			VA05060237	0.90
							cb	2																					
2	6	0.4	0.8	35		20	q/chl	3		30			70.0					2.0											
							cb	2																					
4	6	1.3	2.4	45	55	40	q/cb	4		80	5.0		10.0									B382132	176.16	176.78	**0.350**			VA05060237	0.62
							chl	2																					
1	1	0.5	0.5	50									5.0														same selvage as sulph veins above		
2	6	0.4	0.7	25			q/cb	4					70.0									B382133	176.78	178.31	**0.069**			VA05060237	1.53
							chl	3																					
5	1	2.0	4.5	60		10	q/cb	4					5.0									B382134	178.31	179.18	**0.078**			VA05060237	0.87

DRILL LOG LEGEND P1	DATE: July 4-8, 2005 PAGE 15 of 16		
DRILL HOLE # : DG05-290C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		181.36	187.76	Unalt'd GND between selvages of qtz and sulphide veins. Less carbonate and fewer (but larger) veins. Unalt'd GND in between selvages, up to 50cm long, making up 25% of section. Slickensides in aspy on fract'd veinlet face. From 186.21-186.46m, carbonate is pervasive for 24cm. Clear boundaries at 80° to CA.	0	1	2	1	2	
10		187.76	190.20	Zone with qtz veins and large chl-cb selvages separated by unalt'd GND, in length up to 10cm (15% of section). Slickensides seen on broken sulphide vein face in ox'd py and ser.	1	1	2	1	2	
10		190.20	195.07	Unalt'd GND w/ small grey qtz/carb veins (<0.5cm, mostly). Few grey qtz veins up to 1cm wide; one grey qtz/carb vein 2cm wide. Veinlets of carbonate overprint qtz veins, sometimes using same pathway, others not. Approx 14 carb veinlets/metre.	0	0	1	0	1	
10		195.07	195.67	Top of section is 2cm qtz-carb-sulph vein, followed by 47cm of carb-infused crumbly GND w/ three 1cm sulph veins. One sulph vein (100% ox'd py) and 5cm selvage at end of sample.	1	1	1	2	3	
10		195.67	196.90	Unalt'd GND w/ aspy-rich qtz veins w/ small selvages	0	0	1	0	1	
			(EOH)							

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 4-8, 2005

LOGGED BY: M Stone

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							chl	2																					
2	4	0.4	0.8	45																							same selvage - 2 vein types		
3	6	0.3	0.9	30	140		q/cb	4														B382135	179.18	179.83	0.042			VA05060237	0.65
							chl	2																					
																						B382136	BLANK		<0.005			VA05060237	
4	1	1.0	4.0	60		40	q/cb	4					8.0									B382137	179.83	180.51	0.090			VA05060237	0.68
							chl	2																					
5	1	1.6	4.1	75	50	85	q/cb	4					5.0					5.0				B382138	180.51	181.36	0.180			VA05060237	0.85
							chl	2																					
2	6	0.6	0.9	40	65					70																	same selvage		
5	3	0.5	2.5	45	30	3	cb/q	3	0				20.0									B382139	181.36	182.88	0.128			VA05060237	1.52
							chl	3																					
8	1	12.0	19.0	35	50	14	cb/q	4	0	5			30.0									B382140	182.88	184.40	0.358			VA05058634	1.52
							chl	3																					
4	1	0.5	2.0	30		4	cb/q	2					30.0									B382141	184.40	185.49	0.086			VA05058634	1.09
							chl	1																					
4	1	0.5	2.0	30		4	cb/q	2					30.0									B382142	184.40	185.49	0.079	DUP		VA05058634	1.09
2	4	3.0	4.0	80		24	cb	4					10.0									B382143	185.49	186.46	0.054			VA05058634	0.97
3	1	20.0	22.0	60	50	10	q/cb	3					20.0									B382144	186.46	187.76	0.501			VA05058634	1.30
							chl	2																					
8	1	2.5	6.0	50	60	20	q/cb	3					10.0									B382145	187.76	188.77	0.168			VA05060237	1.01
							chl	2																					
1	6	1.2	1.2	55						30			60.0					4.0				B382146	188.77	190.20	0.122			VA05060237	1.43
3	1	0.5	1.1	50		0.2	q/chl	2	0				8.0									B382147	190.20	191.32	0.018			VA05060237	1.12
4	1	0.7	1.5	35	45	0.5	q/chl	2	0				5.0									B382148	191.32	192.02	0.034			VA05060237	0.70
4	1	0.7	1.5	35	45	0.5	q/chl	2	0				5.0									B382149	191.32	192.02	0.034	PD/CA		VA05060237	0.70
																						B382150	STANDARD 7G		4.520	7G		VA05060237	
7	1	0.6	2.4	30		1	q/cb	3		10			20.0									B382151	192.02	193.55	0.022			VA05060237	1.53
7	1	0.4	2.0	60		2	q/chl	0			3.0		3.0						1.0			B382152	193.55	195.07	0.024			VA05058634	1.52
							cb	2																					
1	3	2.0	2.0	55		10	cb/chl	3		20								4.0				B382153	195.07	195.67	0.202			VA05058634	0.60
							q/s	1																					
3	6	1.5	30.0	55	25	15	cb/chl	3		90			10.0					4.0												
							q/s	1																					
4	1	1.0	4.0	40		4	cb/chl	3					35.0									B382154	195.67	196.60	0.024			VA05058634	0.93
							q	1																					
3	1	1.0	2.0	50		4	cb/chl	3	0				40.0									B382155	196.60	196.90	0.094			VA05058634	0.30
							q	1																					
																						B382156	BLANK		<0.005			VA05058634	
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-291C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 936m

BEARING: 000 | DIP: -50°

DATE STARTED: 25-Jun-05 | DATE COMPLETED: 16-Jul-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459506 NORTHING: 7099243

COORD SYSTEM: NAD 83: EASTING: 459387 NORTHING: 7099427

NAD 27 (CORRECTED for historic grid): EASTING: 459476 NORTHING: 7099253

SECTION LINE(historic grid): 459476

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 5.18m

Deviation:

Casing: 5.18m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

SAMPLING DETAILS

Sample Sequence: B381879 to B381926
Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Jul-05
Lab Record #: VA0506023, VA05058634 Date Received: 21-Jul-05, 16-Jul-05

Sample Sequence: B382157 to B382216
Requisition #: MASP448STRGOL.05Q Date Shipped: 15-Jul-05
Lab Record #: VA05060971 Date Received: 26-Jul-05

Sample Sequence: B382217 to B382333
Requisition #: MASP448STRGOL.05Q Date Shipped: 17-Jul-05
Lab Record #: VA05060214 Date Received: 22-Jul-05

Sample Sequence: B382334 to B382386
Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05
Lab Record #: VA05062470 Date Received: 27-Jul-05

Notes: Hole was abandoned June 26th due to encroaching forest fire. Reopened July 9th.

Duplicates:	B391882, B381902, B381922, B382162, B382182, B382202, B382222, B382242, B382262, B382282, B392302, B382322, B382342, B382362, BB382382
Preparation Duplicate/ Check Assay:	B391889, B381909, B382169, B382189, B382209, B382229, B382249, B382269, B382289, B382309, B382329, B382349, B382369,
Standards:	B391890(4D), B381910(6F), B382170(4D), B382190(5E), B392210(2B), B382230(6F), B382250(7G), B382270(3C), B382290(2B), B382310(4D), B382330(5E), B382350(6F), B382370(7G),
Blanks:	B381896, B381916, B382176, B382196, B382216, B382236, B382256, B382276, B382296, B382316, B382336, B382356, B382376

FROM	TO	LITHOLOGY
5.18	266.57	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
51.8	334.9	-51.0	000.9	001.9
125.0	336.1	-50.6	002.1	003.1
200.0	339.9	-46.6	005.9	006.9
266.7	341.5	-42.5	007.5	008.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: June 26 to July 16, 2006	PAGE 1 of 16		
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-5.18m			CASING; no recovery						
10	5.18-266.57m			GND						
10		5.18	10.67	GND: 15% qtz, 20% feldspar, 30% hbl, 35% bt. Qtz veins (max 1cm) with silicified selvages, up to 20cm wide. Granular appearance w/ oxidation of feldspars to light yellowish orange. Hem ox'd to reddish black w/in veins (~5%). Calcite crystallized on veinlets/fracture faces. Overall, rock is fractured to crumbly sand texture. Xenolith of argillite w/in GND at 5.25m. Finely laminated, dark grey-black. Size is 6cm by 5cm. Type '3' veins are 85% grey, opaque qtz and 15% white opaque calcite throughout. Magnetite is <2mm grains, concentrated near margins of veins; hematite distributed in veins, grains <2mm, up to 8%.	1	0	0	0	1	
10		10.67	12.19	Broken to gravel-sized silicified GND. Mafic minerals reduced to <10%.	1	0	0	0	1	
10		12.19	13.72	More competent, slightly silicified GND. Texture predominantly erased.	1	0	0	0	1	
10		13.72	20.61	GND. Original composition (as at 5.18m). More competent. Only 5% of section is gravelly/sandy, rest are in sections up to 40cm long. Sulphides concentrated at margins (not within) of veins; veins are milky qtz, 50% have grey qtz <3mm wide in centres. Black ox'd magnetite seen on fracture faces. Between veins, thin film of black, <1mm. Metallic mineral, soft hexagonal to tabular, ox'd to black and green: chalcocite (?), throughout GND. Noticeable large grains, up to 1cm in diameter or 3cm long.	1	0	0	0	1	
10		20.61	21.79	V broken to sandy gravel texture. GND oxidized on fracture faces and throughout crumbly sections. Rusty orange brown ox'n product of hematite/limonite.	2	0	0	0	1	
10		21.79	28.50	Competent core with moderate recovery (65%); composition GND as at 5.18m (mafic). At 27.25m, aplite vein (4cm) is cross-cut by 1cm qtz vein. Aspy associated w/ aplite is conc at this intersection.	1	0	0	0	1	
10		28.50	31.32	Crumbly and broken GND. One 10cm gouge section w/ 10% clay, 90% sand, brown, contacts GND at 20°	2	0	0	1	1	
10		31.32	35.05	GND as at 5.18m	1	0	0	0	1	
10		35.05	45.72	50% unalt'd GND as above, 50% crumbly to sandy v. broken up rock. Alternates between them at 0.5m intervals. Recovery averages 50%. Most loss occurs at broken sections. Samples separated where changes occur.	2	0	0	1	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 25 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

PAGE 2 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max. (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopynite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	3	0.8	3.8	30	60	2.0	q/cb	3,1	1													B381879	5.18	6.10	0.022			VA05060237	0.92
2	7	2.5	5.0	45		6.0	q/k	2,1	1													B381880	6.10	7.62	0.105		qtz in pieces	VA05060237	1.52
2	1	2.0	4.0			2.0	q	3	1													B381881	7.62	9.14	0.049			VA05060237	1.52
1	1	0.5	0.5	60		1.0	q	4	1													B381882	7.62	9.14	0.023	DUP		VA05060237	1.52
1	1	0.5	0.5	60		1.0	q	4	1													B381883	9.14	9.53	1.900			VA05060237	0.39
1	1	5.0	5.0	30		20.0	q	4	1													B381884	9.53	10.67	0.088			VA05060237	1.14
3	1	2.0	5.0	60		1.0	q	2	0													B381885	10.67	12.19	0.162			VA05060237	1.52
2	1	2.0	3.0			20.0	q	3	1													B381886	12.19	13.72	0.128			VA05060237	1.53
3	1	1.5	2.5	60	30	20.0	q	3	1													B381887	13.72	15.24	0.061			VA05060237	1.52
4	1	1.2	2.8	40	50	1.0	q/cb	2	1				5.0						1.0			B381888	15.24	16.76	0.122			VA05058634	1.52
1	7	6.0	6.0	55		5.0	q	2	1													B381889	15.24	16.76	0.069	PD/CA		VA05058634	1.52
1	7	6.0	6.0	55		5.0	q	2	1													B381890	STANDARD 4D		0.452	4D		VA05058634	
4	1	1.2	3.0	50		6.0	q	2	2	0.1			0.1					5.0				B381891	16.76	18.29	0.074			VA05058634	1.53
3	1	2.0	3.0	50		6.0	q/chl	3,1	1	6.0			5.0					2.0	1.0			B381892	18.29	19.81	0.043			VA05058634	1.52
							k	1																					
1	1	0.6	0.6	50		4.0	q/k	2	3				2.0						2.0			B381893	19.81	20.61	0.034			VA05060237	0.80
2	1	1.0	1.5	50		3.0	chl/q	2,1	1				2.0						3.0			B381894	20.61	21.79	0.011			VA05060237	1.18
5	1	1.2	4.3	25	60	1.0	q	1	2				3.0						0.0			B381895	21.79	22.91	0.249			VA05060237	1.12
																						B381896	BLANK		<0.005			VA05060237	
3	1	0.8	2.0	30	50	0.5	q	2	1				10.0						3.0			B381897	22.91	24.38	0.090			VA05058634	1.47
1	7	1.4	1.4	60		0.5	chl/k	1	1																		7=aplite dykes		
1	2	0.5	0.5	150		0.5	q/k	1,3	3								20.0	4.0									other=chalcocite		
3	2	1.0	3.0	20		2.0	q/k	3	3				5.0						4.0			B381898	24.38	25.91	0.049			VA05058634	1.53
							chl	1																					
1	1	3.0	3.0	60		1.0	q/chl	1	1								10.0												
3	1	2.0	3.5	50		2.0	q/cb	3,1	2	5.0			10.0				5.0	5.0	4.0			B381899	25.91	27.43	0.062			VA05058634	1.52
1	7	4.0	4.0	115		0.0							5.0						4.0										
1	2	0.5	0.5	55		0.5	q/k	1,2	2													B381900	27.43	28.50	0.567			VA05060237	1.07
1	1	1.0	1.0			1.0	q	1	1													B381901	28.50	29.49	0.156			VA05060237	0.99
1	1	1.0	1.0			1.0	q	1	1													B381902	28.50	29.49	0.109	DUP		VA05060237	0.99
0																						B381903	29.49	30.45	0.013			VA05060237	0.96
1	1	1.0	1.0			0.5	q	1	0													B381904	30.45	31.32	0.252			VA05060237	0.87
1	2	0.5	0.5			0.5	q/k	1	2																				
5	2	2.5	5.0	50		1.0	q/k	3,2	2	8.0			2.0					2.0				B381905	31.32	32.32	0.410			VA05060237	1.00
							chl	1																					
1	2	0.5	0.5	65		1.0	q/k	3,1	1													B381906	32.32	33.53	0.261			VA05060237	1.21
7	1	1.0	4.0	60	30	2.0	q/chl	3,2	1	10.0			8.0					5.0	2.0			B381907	33.53	35.05	0.267			VA05060237	1.52
3	1	0.5	1.5	50		2.0	q	3	1				2.0						1.0			B381908	35.05	36.58	1.185			VA05060237	1.53
3	1	0.5	1.5	50		2.0	q	3	1				2.0						1.0			B381909	35.05	36.58	1.050	PD/CA		VA05060237	1.53
																						B381910	STANDARD 6F		2.860	6F		VA05060237	
3	1	1.5	4.0	60		1.0	q	3	3	0.1								5.0				B381911	36.58	38.10	0.079			VA05060237	1.52
2	1	1.5	3.0	60		0.0				2.0								5.0				B381912	38.10	39.30	0.248			VA05060237	1.20
2	1	0.4	0.8	60	30	0.5	q	3	1	0.1												B381913	39.30	39.62	0.011			VA05060237	0.32
3	1	0.5	1.5	60		10.0	q/chl	3,1	3	3.0			2.0						4.0			B381914	39.62	41.15	0.077			VA05058634	1.53
							k	3																					
2	1	1.0	2.0	15		0.5	q	3	0	0.1								5.0				B381915	41.15	42.67	0.190			VA05058634	1.52
																						B381916	BLANK		<0.005			VA05058634	
5	1	1.0	4.5	45	150	2.0	q/chl	3,1	2	3.0								5.0				B381917	42.67	43.17	0.328			VA05058634	0.50
0																						B381918	43.17	44.05	0.015			VA05058634	0.88
3	1	1.0	3.0	30	60	1.0	q/cb	3	1	5.0								4.0				B381919	44.05	44.74	0.026			VA05060237	0.69
1	3	1.0	1.0	15		10.0	q/cb	4,3	3	0.1								5.0				B381920	44.74	45.72	0.049			VA05060237	0.98

DRILL LOG LEGEND P1	DATE: June 26 to July 16, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		45.72	49.76	Limonite coats fracture faces, 1mm thick. Opaque orange-med brown. Pervasive limonite through core at 46.0-49.76m	3	0	0	1	2	
10		49.76	51.82	GND as at 5.18m, broken with lim on fewer fract faces	2	0	0	1	1	
10		51.82	55.55	Dark grey, partially silicified GND. One 15cm broken up section at 52.40m to coarse sand texture (qtz eyes, etc). Minor limonite and calcite on fracture face, generally at 40° and 15° to CA. In qtz/carb veins, ox'n appears as limonite.	1	0	0	0	1	
10		55.55	57.91	V coarse-grained qtz-rich GND. Euhedral bt up to 6mm in diameter. Disseminated aspy throughout, assoc. w/ bt. Feldspars weathering to clay minerals. Coherent core, however, w/ moderate to good recovery. This rock appears to be alt'd due to veining, as its contact is at 45° to CA (same as veins). Lim staining in wide (up to 5cm) selvages around veinlets.	1	0	1	0	1	
10		57.91	62.48	Lim staining 80% pervasive over section of otherwise unalt'd GND. Qtz veins have small qtz-alt'd selvages dominated by lim. V minor chl in selvage of qtz vein @ 61.00m. GND texture preserved throughout.	3	0	0	0	1	
10		62.48	64.01	GND texture 90% erased in this section, to aphanitic dark grey. v. broken up w/ limonite in wider veins (~2mm) w/ calcite. at 63.70m, a 1.5cm angular qtz piece is surrounded by hexagonal shaped concentration of mafic (bt) material.	4	0	0	1	2	
10		64.01	68.58	Unalt'd GND w/ lim on fract faces (10°-30° to CA); qtz veins partially silicified. Older episodes of veining not recorded, because these veins are too difficult to distinguish well.	1				1	
10		68.58	70.25	GND. Very broken up w/ lim on regular fracture sets at 30° and 130°. Start out 'clean' and go to crumbly and more irregular. Two types qtz veins: (1) large, milky, and (2) small w/ thin, central grey qtz with milky selvages. Evidence of motion w/in minerals: shear bands along 2 planes of motion.	2			1	1	
10		70.25	71.94	Gradation from crumbly, ox'd and carb'd GND above to unalt'd GND below. Silicified selvage on one vein, none on other.	1				1	
10		71.94	75.49	Unalt'd GND. Straight and clear qtz veins w/ little silicified selvages. Po appears, and lots of scorodite w/ aspy.	0	0	0	0	0	
10		75.49	76.02	Extreme alt'n around 3 qtz veins. GND texture totally erased to clay texture. Sericitized, chloritized and ox'd.	4	1	3	3	1	
10		76.02	80.25	V minor alt'n in GND with qtz veins	1	1	1	1	1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: June 25 to July 16, 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

#/meter	Type	VEINS Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Selvages Max (cm)	Alteration	(0-5)	Ox. State 0-5	% of VEIN & DISSEMINATED MATERIAL Sulphides pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation oxide	scordite	biotite	other	Sample Number	Interval From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	1	1.0	1.5	20		1.0	q	3	2	5.0								5.0				B381921	45.72	47.24	0.023			VA05060237	1.52
2	1	1.0	1.5	20		1.0	q	3	2	5.0								5.0				B381922	45.72	47.24	0.013	DUP		VA05060237	1.52
3	1	1.0	2.5	60		0.5	q	3	3	0.1								5.0				B381923	47.24	48.77	0.201			VA05060237	1.53
2	1	3.0	5.0	50		3.0	q	3	2						5.0			5.0				B381924	48.77	49.76	0.033			VA05060237	0.99
0																						B381925	49.76	50.29	<0.005			VA05060237	0.53
4	1	0.4	1.6	40		1.0	q	3	1				10.0									B381926	50.29	51.82	0.181		E.O.H. June 25 (abandoned due to encroaching fire)	VA05060237	1.53
3	1	1.0	3.0	25	50	0.5	q/cb	3	1				1.0						3.0			B382157	51.82	53.34	0.114		grey qtz	VA05060971	1.52
1	3	0.7	0.7	40		2.0	q/cb	3	0				2.0																
6	1	1.1	4.5	40	15	5.0	q/chl	3	0	8.0		3.0	1.0						1.0			B382158	53.34	54.86	0.499			VA05060971	1.52
							cb	1																					
2	3	0.5	0.8				cb	3	1																				
3	1	1.0	3.0	30		0.0				2.0			0.1					5.0				B382159	54.86	55.55	0.143		carb vein areas all broken up - no angles	VA05060971	0.69
2	4	0.2	0.4	45		2.0	cb	2	2				10.0						4.0			B382160	55.55	56.34	0.266		lots of bt assc. w/ veins	VA05060971	0.79
4	1	6.0	9.5	60		2.0	q	3	2	2.0								5.0				B382161	56.34	57.91	2.120			VA05060971	1.57
1	3	0.4	0.4	70									2.0																
4	1	6.0	9.5	60		2.0	q	3	2	2.0								5.0				B382162	56.34	57.91	2.300	DUP		VA05060971	1.57
1	3	0.4	0.4	70									2.0																
3	1	2.0	5.0	45		2.0	q/chl	3	1				12.0						2.0			B382163	57.91	59.44	0.454			VA05060971	1.53
3	1	2.5	4.5	50		2.0	q/cb	3	1				10.0						1.0			B382164	59.44	60.96	0.206			VA05060971	1.52
1	3	1.0	1.0	150		0.0				2.0								5.0									carb crosscuts qtz vein		
4	1	0.5	2.0	30	40	4.0	q/cb	3	2	6.0			2.0					4.0	1.0			B382165	60.96	62.48	0.113			VA05060971	1.52
							chl	1																					
1	1	1.0	1.0	50		0.0				3.0			2.0					5.0	2.0			B382166	62.48	63.55	0.027			VA05060971	1.07
1	1	1.0	1.0	20		1.0	q	1	2				10.0						2.0			B382167	63.55	64.01	0.119			VA05060971	0.46
2	1	0.3	0.6	30	120	1.0	q	2	0	1.0			2.0									B382168	64.01	65.53	0.116			VA05060971	1.52
1	3	0.3	0.3	30		1.0	q/cb	3	2				10.0						3.0										
2	1	0.3	0.6	30	120	1.0	q	2	0	1.0			2.0									B382169	64.01	65.53	0.093	PD/CA		VA05060971	1.52
1	3	0.3	0.3	30		1.0	q/cb	3	2				10.0						3.0										
																						B382170	STANDARD 4D		0.189	4D		VA05060971	
5	1	1.5	4.0	25	155		q	3					8.0						4.0			B382171	65.53	67.06	0.007			VA05060971	1.53
							cb/chl	1																					
8	1	1.0	6.0	30	150	2.0	q	3	2	5.0			5.0					5.0	4.0			B382172	67.06	68.58	0.044			VA05060971	1.52
1	1	1.0	1.0	60		1.0	q	2	1				5.0						1.0			B382173	68.58	69.32	0.005			VA05060971	0.74
3	1	5.0	8.0	35	70																	B382174	69.32	70.25	0.196			VA05060971	0.93
1	1	0.5	0.5	55		1.0	q	4	2				5.0						2.0										
0																						B382175	70.25	71.00	0.024			VA05060971	0.75
																						B382176	BLANK		<0.005			VA05060971	
1	1	2.0	2.0	30		3.0	q	2	1				20.0						2.0			B382177	71.00	71.94	0.040			VA05060971	0.94
1	1	10.0	10.0	140																									
7	1	3.0	7.0	50	30	3.0	q	3	1		9.0		15.0						4.0			B382178	71.94	73.15	0.122			VA05060971	1.21
							chl	1																					
4	1	1.0	3.0	30	130	1.0	q	3	1				15.0						3.0			B382179	73.15	74.68	0.067			VA05060971	1.53
							cb	1																					
3	4	0.2	0.6	25	40	10.0	cb	2	0				40.0						3.0										
2	1	0.3	0.6	35		1.0	q/cb	3					40.0						5.0			B382180	74.68	75.49	0.104			VA05060971	0.81
3	1	1.5	2.5	45		45.0	q/chl	4	4				2.0						4.0			B382181	75.49	76.02	0.124			VA05060971	0.53
							cb/s	2																					
3	1	1.5	2.5	45		45.0	q/chl	4	4				2.0						4.0			B382182	75.49	76.02	0.146	DUP		VA05060971	0.53
6	1	3.0	9.0	40	140	2.0	q	3			4.0		15.0						3.0			B382183	76.02	77.72	0.160		only one vein at 140° (overprinted by one at 40°).	VA05060971	1.70
							cb/chl	1	1																				
1	1	0.8	0.8	30		4.0	q/chl	2					10.0						3.0			B382184	77.72	79.25	0.621			VA05060971	1.53
							cb	1	1																				
3	3	0.2	0.6	45		1.0	q/chl	2			3.0																		
							cb	1	1																				
6	1	2.5	6.5	15	35	6.0	q/chl	2					25.0						2.0			B382185	79.25	80.25	0.804		ox'n in selvages assc. w/ carb	VA05060971	1.00

DRILL LOG LEGEND P1	DATE: June 26 to July 16, 2006	PAGE 5 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		80.25	82.18	Mod'ly to highly alt'd GND. Broken up and alt'd to clayey to coarse sand texture. Carb veins parallel to CA have slickensides in ser and carb.	3	2	2	2	2	
10		82.18	83.96	Mod alt'd GND around veins. From 83.5 to 83.82m, core is bleached, crumbly white around dark grey sulphide veins	2	1		1	1	
10		83.96	89.11	Unalt'd GND. Straight qtz veins with small silicified selvages.						
10		89.11	90.32	Abrupt change (due to recovery loss?) to bleached, clay-rich extremely alt'd GND. Colour is pale grey - white w/ lenses of ox'd sulphides up to 0.7cm wide. GND texture erased. Soft and crumbly.	1	2	3	3	3	
					0	1	2	0	1	
10		90.32	91.44	Competent hard rock. Silicified GND separated by chl-rich selvages around qtz veins.						
10		91.44	94.93	Same as previous but veinlets of carbonate more prevalent, up to 20 per metre in random orientations, in irregular lines	1	1	2	2	2	
10		94.93	115.82	Highly to extremely alt'd GND. Ser + chl +cb alt'n overprints original GND texture. Colour pale greenish white. Ox'd py in veinlets to veins, usually at 0-25° to CA. Qtz veins visible in places, but generally overprinted by alt'n. 80% competent rock, 20% clay texture (carb + ser). At 106.45m, slickensides in ser and carb on vein face at 0° to CA. Slickens @50° to CA on face.	1	3	3	3	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 26 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							cb	2	1																				
5	1	1.5	4.5	60	140	1.0	q	2														B382186	80.25	80.77	0.565			VA05060971	0.52
							chl/cb	1	1																				
6	1	1.5	5.0	30	130	1.0	q	2		2.0	2.0		8.0					5.0	3.0			B382187	80.77	82.18	1.000			VA05060971	1.41
							chl/cb	1	1																				
1	4	1.0	1.0	0		1.0	chl/cb	3		0.1								5.0									carb veins parallel to CA		
							q/s	1,3																					
5	1	1.5	6.0	45	65	2.0	q	3	1	3.0	4.0		5.0						3.0			B382188	82.18	83.50	0.360			VA05060971	1.32
1	4	0.5	0.5	0		0.5	cb	3	3																				
5	1	1.5	6.0	45	65	2.0	q	3	1	3.0	4.0		5.0						3.0			B382189	82.18	83.50	0.376	PD/CA		VA05060971	1.32
1	4	0.5	0.5	0		0.5	cb	3	3																				
																						B382190	STANDARD 5E		1.490	5E		VA05060971	
4	6	1.0	2.5	75		30.0	cb/q	5	2	60.0								5.0				B382191	83.50	83.96	0.266		py is ox'd and v. f-grained	VA05060971	0.46
							k	5																					
2	1	1.0	1.4	25	45	4.0	q	3			10.0		4.0						1.0			B382192	83.96	85.34	0.270			VA05060971	1.38
							chl	1																					
5	1	1.0	3.5	40	10	1.0	q	3			10.0		4.0						2.0			B382193	85.34	86.87	0.812			VA05060971	1.53
							chl	1																					
7	1	1.5	6.0	40	60	3.0	q	1		1.0	6.0		12.0						3.0			B382194	86.87	88.39	0.320			VA05060971	1.52
							chl	2																					
2	1	0.6	1.0	20	40	1.0	q	3			4.0											B382195	88.39	89.11	0.036			VA05060971	0.72
																						B382196	BLANK		<0.005			VA05060971	
5	6	0.7	2.0	60		121.0	s/chl	3	1	100.0								5.0				B382197	89.11	90.32	0.266		ox'd clay sulphides	VA05060971	1.21
							cb	4																					
6	1	1.0	5.0	40	60	5.0	q/chl	4					3.0									B382198	90.32	91.44	0.138			VA05060971	1.12
							s/cb	1																					
2	4	0.5	1.0	40		10.0	q/chl	4		60.0			10.0					4.0											
							cb/s	2	1																				
5	1	2.0	7.0	70	120	4.0	q/chl	4		10.0			2.0					2.0				B382199	91.44	92.96	0.097			VA05060971	1.52
							cb	2																					
2	4	0.2	0.4	45	15	0.0																							
6	1	2.5	9.0	50		20.0	q/chl	4			3.0		9.0									B382200	92.96	94.49	0.140			VA05060971	1.53
5	4	0.5	1.5	20	75		cb/s	2																					
5	6	0.2	1.0	80	100	44.0	q/chl	3	1	80.0								3.0				B382201	94.49	94.93	0.222			VA05060971	0.44
							s/cb	3																					
5	6	0.2	1.0	80	100	44.0	q/chl	3	1	80.0								3.0				B382202	94.49	94.93	0.306	DUP		VA05060971	0.44
2	1	1.0	2.0	60		50.0	chl/s	4		3.0			3.0					5.0				B382203	94.93	96.01	0.081		selvage for both vein types	VA05060971	1.08
							cb/q	2																					
2	3	1.0	2.0	40	70					3.0			3.0																
4	1	1.0	4.0	40			s/chl	4														B382204	96.01	97.54	0.119		selvage extends beyond sample boundaries	VA05060971	1.53
							cb/q	3																					
1	6	0.5	0.5	35						90.0								4.0											
9	1	1.0	5.0	40			s/chl	4		5.0			2.0					3.0				B382205	97.54	99.06	0.245			VA05060971	1.52
							cb/q	3																					
1	6	1.0	1.0	40			q/cb	4		60.0								4.0											
							s/chl	4																					
3	1	1.0	2.0	40	60		chl/q	4	0	2.0			8.0					5.0	1.0			B382206	99.06	100.58	0.105		whole section alt'd selvage	VA05060971	1.52
							s/cb	3																					
3	6	0.2	0.6	10	20		chl/q	4		100.0								5.0				B392207	100.58	102.11	0.164		ox'd clay py	VA05060971	1.53
							s/cb	3																					
2	3	0.5	1.0	15			chl/q	4		5.0			5.0					5.0	3.0			B392208	102.11	103.63	0.122			VA05060971	1.52
							s/cb	3																					
2	3	0.5	1.0	15			chl/q	4		5.0			5.0					5.0	3.0			B392209	102.11	103.63	0.110	PD/CA		VA05060971	1.52
																						B392210	STANDARD 2B		2.870	2B		VA05060971	
3	3	0.5	1.5	20			chl/q	4		10.0			6.0					5.0				B382211	103.63	105.16	0.539			VA05060971	1.53
							s/cb	3																					
2	6	0.2	0.4	0	30		chl/q	4		90.0								5.0									10% carb		
							s/cb	3																					
3	4	0.4	0.2	0	20		chl/q	4		40.0								5.0				B382212	105.16	106.68	0.065			VA05060971	1.52
							s/cb	3																					
2	1	1.0	2.0	30	40					3.0	2.0		5.0					5.0											
4	6	0.4	1.2	20	40		chl/q	4		100.0								4.0				B382213	106.68	107.57	0.045			VA05060971	0.89

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 7 of 16	
DRILL HOLE # : DG05-291C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		115.82	123.44	Minor alt'd GND. Broken up due to carb-infusion from 115.82 to 117.05m. 95% unalt'd GND. Silicified and chl'd qtz vein selvages are the only alt'n besides minor carb veining through rest of section (below 117.05m).	0	0	1	1	1	
10		123.44	125.61	Carb-infused GND. Veinlets and throughout matrix of GND causes rock to be soft and crumbly			1	2	3	
10		125.61	129.84	Back to unalt'd GND. Sheeted qtz veins with silicified/ chloritized selvages. Late calcite with qtz is up to 20% of veins.			1		2	
10		129.84	131.16	Chloritized and carb'd coherent rocks.		1	3	1	2	
10		131.16	134.56	Unalt'd GND w/ sheeted qtz veins. At 134.11m, slickensides on fract face at 45° to CA, in ser +carb+chl+ox'd py (soft clay material).		1	1		1	
10		134.53	139.38	Increased carbonate content (up to ~10% of section) causes rock to appear somewhat bleached. Texture soft and easily broken, crumbly over 40%. Qtz veins continue, selvages with ser + chl still visible, silicified sections more competent than non-sil.		1	1	1	2	
10		139.38	144.78	Highly alt'd GND, w/ carb becoming pervasive in some sections up to 40cm long. Rock is carb-clay soft and crumbly. Chl also intense. Colour med greenish grey.		1	2	2	3	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 25 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

PAGE 8 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							s/cb	3																						
1	3	1.0	1.0	65			chl/q	4		5.0								5.0												
							s/cb	3																						
2	6	0.4	0.8	65						100.0								3.0				B382214	107.57	108.20	0.052		py less ox'd	VA05060971	0.63
2	6	0.3	0.6	35	5					90.0								4.0				B382215	108.20	109.73	0.083			VA05060971	1.53
1	1	0.8	0.8	45						5.0								5.0												
																						B382216	BLANK		<0.005			VA05060971	
5	6	1.0	2.2	10	60					90.0								4.0				B382217	109.73	111.25	0.250			VA05060214	1.52
3	3	1.0	2.0	35						15.0								4.0												
6	4	0.5	1.8	20	40					50.0								5.0				B382218	111.25	112.78	0.059			VA05060214	1.53
1	6	0.5	0.5	50						100.0								5.0												
4	1	1.0	4.0	45						5.0								4.0				B382219	112.78	114.30	0.173			VA05060214	1.52
2	4	2.0	4.0	40						3.0			2.0					5.0												
12	3	0.5	5.0	30	50					10.0	0.1							5.0				B382220	114.30	115.82	0.218			VA05060214	1.52
1	6	0.3	0.3	30						100.0								5.0												
5	1	2.0	7.0	30		1.0	q/chl	3		100.0								5.0				B382221	115.82	117.35	0.146			VA05060214	1.53
4	4	1.0	2.2	30	5					10.0								5.0												
5	1	2.0	7.0	30		1.0	q/chl	3		100.0								5.0				B382222	115.82	117.35	0.047	DUP		VA05060214	1.53
4	4	1.0	2.2	30	5					10.0								5.0												
3	1	1.0	3.0	40	50	2.0	q/chl	3	0		5.0		5.0						2.0			B382223	117.35	118.87	0.089			VA05060214	1.52
6	3	0.2	1.2	10	30																									
5	1	1.0	4.0	50		1.0	q/chl	3	0	2.0	0.1		2.0					4.0	1.0			B382224	118.87	120.40	0.085			VA05060214	1.53
1	6	0.3	0.3	60		4.0	q/chl	4,1	0		5.0		70.0																	
7	1	1.0	4.0	60		2.0	q/chl	3,2			2.0		10.0						2.0			B392225	120.40	121.92	0.084			VA05060214	1.52
11	1	2.0	9.0	45		2.0	q/chl	3,1	0		5.0		10.0						2.0			B392226	121.92	123.44	0.072			VA05060214	1.52
4	1	1.5	3.5	45		1.0	q/chl	3,1	0				5.0						4.0			B392227	123.44	124.97	0.123			VA05060214	1.53
1	1	1.0	1.0	30		1.0	q/chl	3,1					3.0						3.0			B382228	124.97	125.61	0.016			VA05060214	0.64
1	1	1.0	1.0	30		1.0	q/chl	3,1					3.0						3.0			B382229	124.97	125.61	0.102	PD/CA		VA05060214	0.64
																						B382230	STANDARD 6F		2.900	6F		VA05060214	
3	1	0.6	1.4	40		2.0	q/chl	3,2	0		2.0		5.0						3.0			B382231	125.61	126.49	0.275			VA05060214	0.88
7	1	1.0	5.0	35	140	2.0	q/chl	3	0		2.0		5.0						3.0			B382232	126.49	127.28	0.292			VA05060214	0.79
8	1	0.5	4.0	40		2.5	q/chl	3			3.0		8.0						3.0			B382233	127.28	128.02	0.099			VA05060214	0.74
							cb	2																						
8	1	0.5	4.0	40		2.0	q/chl	3			6.0		8.0						4.0			B382234	128.02	128.77	1.990			VA05060214	0.75
							cb	2																						
6	1	0.5	2.0	45		2.0	q/chl	3			8.0		10.0						4.0			B382235	128.77	129.54	0.477			VA05060214	0.77
							cb	2																						
																						B382236	BLANK		<0.005			VA05060214	
2	1	0.4	0.7	50		2.0	q/chl	3					3.0						3.0			B382237	129.54	129.84	0.366			VA05060214	0.30
							cb	2																						
4	1	1.3	3.0	40		150.0	q/chl	4		3.0			5.0	0.1					1.0			B382238	129.84	131.16	0.111		selvage for all veins = 1 sample	VA05060214	1.32
							cb	3																						
12	1	1.0	7.0	45	30	2.0	q	4	0	1.0	8.0		6.0						2.0			B382239	131.16	132.59	0.097			VA05060214	1.43
							chl/cb	1																						
11	1	2.0	10.0	50	35	4.0	q	4		1.0	3.0		6.0						1.0			B382240	132.59	133.34	0.621			VA05060214	0.75
							chl/cb	3,2																						
5	1	2.0	6.5	50	35	8.0	q/chl	3			5.0		2.0						3.0			B382241	133.34	134.11	0.127			VA05060214	0.77
							cb	2																						
5	1	2.0	6.5	50	35	8.0	q/chl	3			5.0		2.0						3.0			B382242	133.34	134.11	0.119	DUP		VA05060214	0.77
6	1	1.0	2.5	40	10	1.0	q/chl	3			5.0		5.0						2.0			B382243	134.11	134.53	0.143			VA05060214	0.42
							cb	2																						
3	1	2.0	5.0	50		1.0	q/chl	2			1.0		10.0						2.0			B382244	134.53	135.63	0.087		20 carb veinlets per metre	VA05060214	1.10
3	4	0.5	1.5	65	40																									
3	1	1.0	3.0	50		1.0	q/chl	2		1.0			8.0									B382245	135.63	136.39	0.100			VA05060214	0.76
1	6	0.5	0.5	65						90.0	1.0							2.0												
2	1	1.0	2.0	50		2.0	q/chl	3		1.0			10.0					5.0	2.0			B382246	136.39	137.30	0.062			VA05060214	0.91
5	4	0.2	1.0	40		1.0	cb	2																						
9	1	2.5	6.5	40	50	2.0	q/chl	4		4.0			5.0					5.0	2.0			B382247	137.30	138.68	1.375			VA05060214	1.38
3	1	1.0	2.6	50	35	1.0	q/chl	3			2.0		10.0						3.0			B382248	138.68	139.38	0.093			VA05060214	0.70
							cb	1																						
3	1	1.0	2.6	50	35	1.0	q/chl	3			2.0		10.0						3.0			B382249	138.68	139.38	0.076	PD/CA		VA05060214	0.70
																						B382250	STANDARD 7G		4.470	7G		VA05060214	
1	3	3.0	3.0	65		40.0	q/chl	2		4.0								5.0				B382251	139.38	140.21	0.322		v. crumbly and soft	VA05060214	0.83

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2006	PAGE 9 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		144.78	156.97	GND, alt'd only around qtz veins (selvages). Sheeted veins at 50° to CA.		1	1		1	
10		156.97	170.69	GND w/ approx 6 qtz veins per metre and 15 carb veinlets per metre of core. Outside selvages and carb'd (crumbly) sections, rock is unalt'd. Colour med grey.		1	1		1	
10		170.69	173.74	Sheeted qtz veins continue through more carb-rich zone. Veinlets of powdery, opaque white carbonate are at 60° and 10° to CA and cause rock to crumble.		1	1		2	
10		173.74	178.31	Selvages dominate core (section is 70% minorly alt'd w/ ser and chl). Less carb means more competent rock. Slickensides on faces at 40° in ser, chl.		2	2		1	
10		178.31	182.88	80% unalt'd GND. 30cm zone of carb-rich. 30cm chloritic selvage around 3 1cm qtz veins. All competent. Slickensides in ox'd and unox'd py on face at 30° to CA.		1	1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 25 to July 16, 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
							cb/s	3																					
5	1	1.0	5.0	40	110	6.0	q/chl	3					3.0						2.0			B382252	140.21	141.73	0.257			VA05060214	1.52
							cb/s	2																					
3	4	0.6	1.8	30	10	10.0	cb	3		3.0								5.0											
5	1	1.2	3.0	25	40	3.0	q/chl	2		2.0		1.0	5.0					4.0	2.0			B382253	141.73	143.26	0.176			VA05060214	1.53
							cb/s	2																					
6	4	0.5	2.0	140	110	2.0	cb	1		10.0								5.0											
4	1	1.0	4.0	50		2.0	q/chl	3		2.0			4.0					3.0	3.0			B382254	143.26	144.78	0.063			VA05060214	1.52
							cb/s	2																					
8	1	1.0	8.0	40	25	2.0	q/chl	4,2		2.0	4.0		8.0						3.0			B382255	144.78	146.30	0.172			VA05060214	1.52
																						B382256	BLANK		<0.005			VA05060214	
9	1	1.5	7.0	45	25	6.0	q/chl	3		1.0	7.0		10.0						2.0			B382257	146.30	147.83	0.060			VA05060214	1.53
							cb	2																					
1	3	1.0	1.0	35		1.5	q/cb	3					15.0						2.0										
							chl	3																					
4	1	2.0	5.0	30	40	2.0	q/chl	4					20.0						1.0			B382258	147.83	148.60	7.760			VA05060214	0.77
							cb	2																					
4	1	3.0	8.0	35		14.0	q/chl	4			5.0		10.0						2.0			B382259	148.60	149.39	0.105			VA05060214	0.79
1	1	1.5	5.0	40		10.0	q/chl	4			3.0		10.0						3.0			B382260	149.39	150.88	0.938			VA05060214	1.49
							cb	1																					
9	1	1.0	7.0	40	35	4.0	q/chl	4			8.0	1.0						1.0				B382261	150.88	152.40	0.200			VA05060214	1.52
							cb	1																					
9	1	1.0	7.0	40	35	4.0	q/chl	4			8.0	1.0						1.0				B382262	150.88	152.40	0.323	DUP		VA05060214	1.52
5	1	1.0	5.0	45		2.0	q/chl	4		2.0	3.0		5.0						1.0			B382263	152.40	153.92	0.391			VA05060214	1.52
							cb	1																					
2	3	1.0	2.0	45	25	1.0	cb	4																					
8	1	2.5	6.0	40	60	3.0	q/chl	4			2.0		4.0									B382264	153.92	155.45	0.080			VA05060214	1.53
1	4	10.0	10.0	55		20.0	chl/cb	4		10.0								5.0											
10	1	1.2	10.0	40	60	10.0	q/chl	3		3.0	1.0		8.0						1.0			B382265	155.45	156.97	0.122			VA05060214	1.52
							cb	2																					
6	1	2.0	5.0	10	30	1.0	q/chl	3				1.0	10.0						2.0			B382266	156.97	158.50	0.071			VA05060214	1.53
							cb	1																					
1	4	3.0	3.0	70		26.0	chl/cb	4					0.1																
							q/s	2																					
5	1	2.5	6.0	40		5.0	q/chl	4			2.0		7.0						2.0			B382267	158.50	160.02	0.086			VA05060214	1.52
3	4	0.3	0.9			20.0	cb/s	3																					
							chl	3																					
8	1	3.0	12.0	40		2.0	q/chl	3			5.0		5.0						1.0			B382268	160.02	161.54	0.060			VA05060214	1.52
8	1	3.0	12.0	40		2.0	q/chl	3			5.0		5.0						1.0			B382269	160.02	161.54	0.080	PD/CA		VA05060214	1.52
																						B392270	STANDARD 3C		0.094	3C		VA05060214	
4	3	0.6	1.5	30		2.0	q/chl	3			5.0		5.0						1.0			B392271	161.54	163.07	0.189		aspy slickensides	VA05060214	1.53
							cb	2																					
3	3	1.0	3.0	45		4.0	q/chl	4			8.0		5.0						1.0			B382272	163.07	164.59	0.122			VA05060214	1.52
2	6	0.5	1.0	30		20.0	cb	4	1	60.0								4.0											
							chl	3																					
8	1	1.5	8.0	40	50	1.0	q	3			8.0		5.0						3.0			B382273	164.59	166.12	0.235			VA05060214	1.53
9	1	1.0	5.0	50		1.0	q	4			8.0		5.0						3.0			B382274	166.12	167.64	0.052			VA05060214	1.52
9	1	1.5	6.5	30	45	1.0	q	4			3.0		2.0						3.0			B382275	167.64	169.16	0.197			VA05060214	1.52
							cb	1																					
																						B382276	BLANK		<0.005			VA05060214	
6	1	1.0	4.0	35	70	1.0	q/chl	3			5.0		8.0						3.0			B382277	169.16	170.69	0.044			VA05060214	1.53
5	1	1.0	4.0	40	55	2.0	q/chl	3			10.0		5.0						3.0			B382278	170.69	171.59	0.509			VA05060214	0.90
3	1	1.5	3.5	40		1.0	q	3			10.0											B382279	171.59	172.21	0.129			VA05060214	0.62
8	1	2.0	10.0	45		1.5	q	3			10.0		5.0						1.0			B382280	172.21	173.74	0.231			VA05060214	1.53
							chl	1																					
6	4	0.2	1.2	60	10	0.5	cb	4																					
3	1	2.0	5.0	35		3.0	q/chl	3		3.0	6.0		6.0						3.0			B382281	173.74	175.26	0.052			VA05060214	1.52
3	1	2.0	5.0	35		3.0	q/chl	3		3.0	6.0		6.0						3.0			B382282	173.74	175.26	0.154	DUP		VA05060214	1.52
7	1	5.0	11.0	40	130	4.0	q/chl	3			12.0		6.0						2.0			B382283	175.26	176.78	0.118			VA05060214	1.52
							s/cb	1																					
7	1	1.0	6.0	20	130	12.0	q/chl	4			4.0		5.0						3.0			B382284	176.78	178.31	0.064			VA05060214	1.53
							s/cb	1																					
1	4	0.2	0.2	70		20.0	cb/chl	3		20.0	5.0		5.0					4.0	3.0										
							q/s	3																					
9	1	1.0	7.0	40		3.0	q	3					8.0						3.0			B382285	178.31	179.83	0.397			VA05060214	1.52
5	1	1.0	5.0	40	70	2.0	q	3			2.0		10.0						2.0			B382286	179.83	181.36	0.025			VA05060214	1.53

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2006	PAGE 11 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		182.88	185.93	Another carb-rich zone. White, crumbly carb in veinlets and throughout matrix of GND overprints qtz veins. Some chl'd selvages still visible.		1	1	1	2	
10		185.93	188.98	Mod'ly alt'd GND. Minor carb in veinlets and through 50% of matrix. Qtz veins have silicified and chl'd selvages twice as wide as the veins themselves.	0	2	1	1	2	
10		188.98	192.02	GND texture is 95% erased to aphanitic chloritic/sericitic competent core. One 5cm qtz vein at 196.60m. Colour is medium greyish green, minor veinlets of carbonate overprint rock at low angles (<20° to CA)						
10		192.02	193.55	Highly alt'd GND. Carb (white, powdery) in veinlets and through matrix of GND. Texture crumbly over 60% of section. Competent core up to 15cm long.	1	2	2	2	3	
10		193.55	202.89	Minor to mod alt'n through section, depending on carb infusion amount, sections up to 30cm of mod alt'n. Silicified and chl'd selvages are small around qtz veins.		1	1		1	
10		202.89	204.75	V little carb; qtz veins w/ chl'd selvages interrupt unalt'd GND.		1	1			
10		204.75	208.22	GND infused w/ carb, so crumbly and broken. Sheeted qtz veins continue.		1	1		3	
10		208.22	212.73	Moderate carb alt'n overprints qtz veins and their sil'd, chl'd selvages. At 212.40m, 30cm section of sub-rounded, lim-covered cobbles, ave size 5cm; may be due to late brittle faulting and motion, with influx of lim-rich meteoric waters, or surface waters infiltrating rock and weathering it.	1	1	1	1	2	
10		212.73	216.41	Remnant qtz vein pieces within carb-rich GND. Coherent core (70%) appears sheared, hence the vein destruction. Sulphides in veinlets throughout section.	1	1		2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: June 25 to July 16 , 2006 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

PAGE 12 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
8	1	2.0	7.0	40	150	30.0	q/chl	5		15.0			12.0					3.0	3.0			B382287	181.36	182.88	0.037			VA05060214	1.52
4	1	3.0	5.0	40	70	4.0	q/chl	3		1.0	1.0		10.0						3.0			B382288	182.88	184.40	0.030			VA05060214	1.52
							s/cb	2																					
4	1	3.0	5.0	40	70	4.0	q/chl	3		1.0	1.0		10.0						3.0			B382289	182.88	184.40	0.053	PD/CA		VA05060214	1.52
																						B382290	STANDARD 2B		3.050	2B		VA05060214	
4	1	1.0	3.0	40		1.0	q/chl	3			5.0	1.0	8.0						1.0			B382291	184.40	185.93	0.138			VA05060214	1.53
7	4	0.3	2.0	0	60	4.0	cb	3																					
7	1	2.0	5.0	45	120	4.0	q/chl	3			10.0		5.0						2.0			B382292	185.93	187.45	0.079			VA05060214	1.52
							cb/s	1																					
4	1	2.0	4.0	45	35	2.0	q/cb	3			14.0	2.0	5.0						4.0			B382293	187.45	188.98	0.125			VA05060214	1.53
							chl	1																					
1	4	0.7	0.7	150		4.0	cb/chl	4	1																				
							q	1																					
2	1	1.4	2.4	45		8.0	q/chl	4	1	30.0								1.0				B382294	188.98	190.50	0.063			VA05060214	1.52
							cb	2																					
2	1	5.0	7.0	50		50.0	q/chl	4	1		6.0		10.0						3.0			B382295	190.50	192.02	0.091			VA05060214	1.52
							cb	3																					
6	4	1.0	5.0	55	70	20.0	cb	4		10.0								5.0											
																						B382296	BLANK		<0.005			VA05060214	
8	1	1.0	6.5	50		50.0	q/chl	4														B382297	192.02	193.55	0.170			VA05060214	1.53
							cb	3																					
3	4	1.0	2.0	50		20.0	cb	4		10.0								5.0											
																						B382298	193.55	194.35	0.105			VA05060214	0.80
7	1	2.0	7.4	30	130	6.0	q/chl	4			4.0		15.0						1.0			B382299	194.35	195.07	0.245			VA05060214	0.72
1	4	1.0	1.0	60		20.0	chl/cb	4		10.0								5.0											
8	1	2.5	8.6	50	60	6.0	q/chl	4		15.0	2.0		10.0					2.0	2.0			B382300	195.07	195.74	0.283			VA05060214	0.67
							cb	3																					
9	1	1.5	10.0	70	110	2.0	q/cb	2					20.0									B382301	195.74	196.60	0.078			VA05060214	0.86
1	3	1.0	1.0	90		12.0	cb	2																					
9	1	1.5	10.0	70	110	2.0	q/cb	2					20.0									B392302	195.74	196.60	0.116	DUP		VA05060214	0.86
1	3	1.0	1.0	90		12.0	cb	2																					
5	1	3.0	12.0	50	30	4.0	q/cb	4			10.0		2.0					1.0				B382303	196.60	198.12	0.224			VA05060214	1.52
							chl	2																					
3	1	1.2	3.0	55	35	2.0	q/chl	3			6.0		2.0					3.0	1.0			B382304	198.12	199.64	0.369			VA05060214	1.52
							cb	3																					
6	1	1.0	4.5	60	40	1.0	q	3			8.0		20.0					2.0	1.0			B392305	199.64	201.17	0.092			VA05060214	1.53
2	4	1.0	1.3	0	30	12.0	cb	3					3.0						4.0										
							chl	2																					
1	1	1.0	1.0	50		0.5	q/chl	1														B392306	201.17	202.09	0.104			VA05060214	0.92
2	4	1.0	1.0	30	130	26.0	cb/chl	4		13.0								3.0											
1	1	1.0	1.0	30		3.0	q/chl	2			10.0		5.0					1.0	2.0			B382307	202.09	202.89	0.099			VA05060214	0.80
1	6	0.4	0.4	45		2.0	cb/chl	3		70.0								4.0											
							q	1																					
8	1	2.0	6.0	40	150	18.0	q/chl	4			12.0		2.0					1.0	1.0			B382308	202.89	203.78	0.055			VA05060214	0.89
							cb/s	2																					
8	1	2.0	6.0	40	150	18.0	q/chl	4			12.0		2.0					1.0	1.0			B382309	202.89	203.78	0.066	PD/CA		VA05060214	0.89
																						B382310	STANDARD 4D		0.424	4D		VA05060214	
6	1	2.0	8.0	40	10	3.0	q/chl	3			9.0		5.0					1.0	2.0			B382311	203.78	204.22	0.278			VA05060214	0.44
3	1	2.0	4.0	45		2.0	q/chl	3			10.0		5.0					1.0	3.0			B382312	204.22	204.75	0.113			VA05060214	0.53
7	1	1.2	5.5	50	40	1.0	q/cb	4			5.0		10.0						3.0			B382313	204.75	205.74	0.106			VA05060214	0.99
10	1	1.0	7.0	40	20	3.0	q/chl	3			15.0	3.0	10.0					1.0	4.0			B382314	205.74	207.26	0.045			VA05060214	1.52
							cb/s	2																					
2	1	4.0	5.0	50		2.0	q/chl	3			20.0											B382315	207.26	208.22	0.029			VA05060214	0.96
							cb/s	1																					
																						B382316	BLANK		<0.005			VA05060214	
4	1	1.0	3.5	45	65	8.0	q/cb	4			20.0	1.0										B382317	208.22	208.79	0.132			VA05060214	0.57
							chl/s	1																					
7	1	1.0	7.0	50	25	1.0	q	2			15.0											B382318	208.79	210.31	0.066			VA05060214	1.52
7	1	1.5	5.5	60	25	1.0	q/chl	3,1			15.0		2.0									B382319	210.31	211.84	0.093			VA05060214	1.53
3	1	4.0	7.0	45		1.0	q	3	2													B382320	211.84	212.73	0.136			VA05060214	0.89
2	1	1.0	2.0	45		1.0	q	3			0.1											B382321	212.73	213.36	0.083			VA05060214	0.63
2	1	1.0	2.0	45		1.0	q	3			0.1											B382322	212.73	213.36	0.133	DUP		VA05060214	0.63

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 13 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		216.41	219.03	Veins now unsheared, selvages still present beneath moderate carb alt'n.	2	3	1	2	2	
10		219.03	219.46	Dark grey aphanitic, silicified GND. Dark grey to black clay and carb on fracture faces. Grades into next section...		1	1	2	1	
10		219.46	220.43	Ser/chl/carb alt'n, moderate. GND texture 50% erased to pale whitish green colour.		2	3	1	3	
10		220.43	228.60	Unalt'd GND w/ sheeted qtz veins continuing but with less defined margins - has been 'reheated' or cooled more slowly here than up in hole. Also far less carbonate here; rock is solid. Straight fractures in random orientations. At 221.35m, qtz vein contains ~20% py and has obviously been offset along late sulphide veinlets.		1	1		1	
10		228.60	231.52	Sulphide veins begin, with large selvages of chl, ser (+minor carb) alt'n.	1	2	2			1
10		231.52	223.17	Carbonate content increases so rock is v broken up into lengths less than 10cm.	1	2	2	1	2	
10		233.17	240.09	V minor silicification and chloritization of GND around qtz veins, which are fewer but larger. One 12.5cm grey qtz vein at 237.42m. Sulphide veinlets offset qtz veins sinistrally if qtz veins are at 30° and sulph veins are at 160° to CA. Carbonate appears in few veinlets, later than other veinlets/veins. Concentrated (up to 5%) in 30cm length from 237.56 to 237.86m.	1		1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 25 to July 16 , 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval					
						Selvages				Sulphides										Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	1	1.2	2.2	40		1.0	q/chl	2			6.0		2.0						2.0			B382323	213.36	214.88	**0.120**			VA05060214	1.52
4	1	5.0	10.0	50		0.0				10.0	8.0		3.0					4.0				B382324	214.88	216.41	**0.216**		selvages all sheared away	VA05060214	1.53
3	6	0.3	0.7	30						80.0								5.0									only one vein has orig. angle		
5	1	2.0	7.5	50						3.0	10.0		5.0					5.0	4.0			B382325	216.41	217.93	**0.170**			VA05060214	1.52
1	6	0.7	0.7	30						70.0								4.0											
3	1	1.5	3.5	60	20	1.5	q	3					5.0						3.0			B382326	217.93	219.03	**0.103**			VA05060214	1.10
							chl	1																					
1	4	1.0	1.0	60		2.0	cb/b	2		15.0								5.0											
3	1	1.0	2.0	10	90																	B382327	219.03	219.46	**0.024**			VA05060214	0.43
4	1	2.0	5.0	45		1.0	cb/q	3														B382328	219.46	220.43	**0.097**			VA05060214	0.97
							chl/s	3																					
4	1	2.0	5.0	45		1.0	cb/q	3														B382329	219.46	220.43	**0.177**	PD/CA		VA05060214	0.97
																						B382330	STANDARD 5E		**1.346**	5E		VA05060214	
6	1	2.0	8.0	50		1.0	q	4			5.0		3.0					1.0	3.0			B382331	220.43	220.98	**0.096**			VA05060214	0.55
9	1	3.0	11.0	40		1.0	q	4		10.0	5.0		1.0					2.0	3.0			B382332	220.98	221.59	**0.133**			VA05060214	0.61
5	1	35.0	10.0	50		1.0	q	2			12.0		2.0						3.0			B382233	221.59	222.50	**0.141**			VA05060214	0.91
							chl/s	1																					
5	1	5.0	8.0	45	35	2.0	q/chl	3			6.0		4.0						4.0			B382334	222.50	223.26	**0.526**			VA05062470	0.76
							s	1																					
2	1	1.0	2.0	30		1.0	q	2			3.0		3.0						4.0			B382335	223.26	224.03	**0.035**			VA05062470	0.77
3	6	0.3	0.9	40	140	10.0	q/chl	4		60.0								2.0											
							s/cb	2														B382336	BLANK		**<0.005**			VA05062470	
5	1	1.0	2.5	50	60	2.0	q	2	1		10.0											B382337	224.03	224.63	**0.062**			VA05062470	0.60
6	1	1.5	6.5	40		2.0	q/chl	3			15.0											B382338	224.63	225.55	**0.037**			VA05062470	0.92
							cb	2																					
10	1	2.0	10.0	45	40	2.0	q	2		2.0	10.0		8.0						2.0			B382339	225.55	227.08	**0.083**			VA05062470	1.53
6	1	3.0	9.0	50	70	2.0	q	3			2.0		2.0									B382340	227.08	227.80	**0.177**			VA05062470	0.72
6	1	2.0	6.5	35	70	6.0	q/chl	2			4.0		3.0						2.0			B382341	227.80	228.60	**1.790**			VA05062470	0.80
6	1	2.0	6.5	35	70	6.0	q/chl	2			4.0		3.0						2.0			B382342	227.80	228.60	**0.129**	DUP		VA05062470	0.80
4	1	1.0	4.0	40	130	2.0	q/chl	3			2.0		3.0						2.0			B382343	228.60	230.12	**0.104**			VA05062470	1.52
4	6	0.2	0.8	85		10.0	q/chl	4		80.0								4.0											
							cb/s	3																					
4	1	1.8	3.3	30	40	1.0	q	2			8.0		3.0						4.0			B382344	230.12	231.52	**0.213**			VA05062470	1.40
							chl/cb	1																					
2	6	0.3	0.6	20		4.0	q/chl	4		60.0	10.0		15.0					4.0	4.0										
							cb/s	2																					
3	1	1.5	4.5	40		1.0	q	2		15.0	5.0	1.0						3.0				B382345	231.52	232.42	**0.086**			VA05062470	0.90
							cb/chl	2																					
2	4	2.0	3.0	40	45	12.0	cb/chl	4	1	10.0								5.0											
							q/s	2																					
3	1	2.0	5.0	25		50.0	cb/chl	4	1	10.0	5.0		10.0					4.0	3.0			B382346	232.42	233.17	**0.068**			VA05062470	0.75
							q/s	2																					
4	1	3.0	7.0	35		8.0	q/chl	3			1.0		5.0						4.0			B382347	233.17	234.70	**0.083**			VA05062470	1.53
							cb/s	1																					
3	6	0.2	0.5	55						80.0								4.0											
4	1	1.0	4.0	60	45					8.0	5.0		2.0					4.0				B382348	234.70	236.22	**0.027**			VA05062470	1.52
3	6	0.2	0.6	15	50					100.0								5.0											
4	1	1.0	4.0	60	45					8.0	5.0		2.0					4.0				B382349	234.70	236.22	**0.032**	PD/CA		VA05062470	1.52
3	6	0.2	0.6	15	50					100.0								5.0											
																						B382350	STANDARD 6F		**2.660**	6F		VA05062470	
5	1	12.5	18.5	30		4.0	q/chl	2		2.0	14.0	3.0	15.0		0.1							B382351	236.22	236.98	**3.440**			VA05062470	0.76
							cb/s	2																					
5	6	0.2	1.0	160		0.2	chl/cb	4																					
4	1	2.0	5.0	40		2.0	q/chl	2					3.0									B382352	236.98	237.56	**0.101**			VA05062470	0.58
3	6	0.2	0.6	35	85	0.2	cb/chl	1	1	100.0								5.0											
4	6	0.3	1.0	130		6.0	q/chl	3		97.0		3.0						1.0				B382353	237.56	238.08	**0.069**			VA05062470	0.52
							cb/s	3																					
2	1	0.5	1.0	60		2.0	q/chl	2					7.0																
3	6	0.2	0.6	0	45	1.0	q/cb	2	2	100.0								5.0				B382354	238.08	239.27	**0.105**			VA05062470	1.19
							chl/cb	1																					
4	1	3.0	8.0	55	35	1.0	q/chl	2			10.0	1.0	4.0					1.0				B382355	239.27	240.05	**0.246**			VA05062470	0.78
																						B382356	BLANK		**<0.006**			VA05062470	

DRILL LOG LEGEND P1	DATE: June 25 to July 16, 2005	PAGE 15 of 16	
DRILL HOLE # : DG05-291C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		240.09	240.94	Crumbly carb-infused GND. Veinlets and throughout matrix. Coherent core <10cm long. Clay rich. Ox'd py throughout (from old sulph veins).	2	2	2	1	3	
10		240.94	244.56	Fewer qtz veins in unalt'd GND. Sulph veinlets still offsetting qtz veins, as at 233.17 to 240.09m.	1		1		1	
10		244.56	245.36	Crumbly/clay to competent highly alt'd GND. Chlorite and silicification are pervasive and colour is solid greenish grey. Only qtz eyes left of GND texture. Carbonitic clay contacts are at 125° (upper) and 25° (lower).	2	2	3	2	2	
10		245.36	248.41	Minor to mod carb alt'n throughout. Otherwise unalt'd GND w/ continuing qtz veins and sulphide veinlets.	1	1	1	0	2	
10		248.41	259.08	Unalt'd GND w/ sheeted veins, at lower angles (<10°), for first sample, to 249.94m. Mod to strong slickensides on fracture faces. Solid core.			1		1	
10		259.08	266.57	More carb alt'd GND. Texture is granular, somewhat crumbly but overall GND texture preserved, just softened. Sulphide veins more numerous and bigger - up to 0.5cm wide. Fewer qtz veins, somewhat rearranged by weak foliation parallel to carbonate and sulphide veinlets.	1	1	1	2	3	
			E.O.H.							

DRILL LOG LEGEND - P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: June 25 to July 16, 2005 (stopped June 26-July 10 for fire)

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	3.0	3.0			10.0	q/chl	3	2				6.0						4.0			B382357	240.05	240.94	0.109		qtz pieces	VA05062470	0.89
5	1	1.0	4.0	45		1.0	q/cb	2,1	1		9.0		5.0					1.0	1.0			B382358	240.94	241.66	0.120			VA05062470	0.72
4	6	0.2	0.8	40		2.0	q/chl	4	1	80.0		1.0	5.0					5.0										
1	1	4.0	4.0	40		4.0	q/chl	3	1	10.0	5.0		15.0					2.0	0.0			B382359	241.66	242.32	0.129			VA05062470	0.66
							cb/s	1																				
2	6	0.2	0.4	140		2.0	q/chl	4	2	90.0								5.0										
3	1	4.0	6.0	45		4.0	q/chl	3	2		5.0		5.0						4.0			B382360	242.32	242.98	0.087			VA05062470	0.66
							cb/s	1																				
2	6	0.2	0.4	140		1.0	q	3		90.0		5.0						2.0										
5	1	1.5	5.5	45		2.0	q/chl	2	0		3.0		1.0					2.0	5.0			B382361	242.98	243.84	0.069			VA05062470	0.86
							cb/s	1																				
5	1	1.5	5.5	45		2.0	q/chl	2	0		3.0		1.0					2.0	5.0			B382362	242.98	243.84	0.138	DUP		VA05062470	0.86
2	1	1.0	2.0	55	150	3.0	q/chl	2	1		3.0											B382363	243.84	244.56	0.069			VA05062470	0.72
							cb/s	2																				
1	4	4.0	4.0	125		14.5	cb/chl	4	2	30.0								3.0				B382364	244.56	245.36	0.061			VA05062470	0.80
							s/q	3																				
6	1	2.0	7.0	50		3.0	q/chl	3			5.0		9.0					1.0	3.0			B382365	245.36	246.69	1.770			VA05062470	1.33
							cb	3																				
6	6	0.1	0.6	35		1.0	q/cb	3		100.0								4.0										
5	1	1.3	3.5	35		5.0	q/chl	3		5.0		5.0										B382366	246.69	248.41	0.042			VA05062470	1.72
4	1	3.0	6.0	10	60	2.0	q/cb	3			9.0		10.0									B382367	248.41	249.94	0.419			VA05062470	1.53
5	1	1.3	5.0			1.0	q/chl	2			3.0											B382368	249.94	251.46	0.027		random orientations of veins - all rearranged	VA05062470	1.52
5	1	1.3	5.0			1.0	q/chl	2			3.0											B382369	249.94	251.46	0.028	PD/CA		VA05062470	1.52
																						B382370	STANDARD 7G		4.420	7G		VA05062470	
7	4	0.2	1.4	15																		B382371	251.46	252.98	0.029			VA05062470	1.52
5	1	1.0	5.0	70	50	0.5	q/chl	2	1	40.0	40.0							3.0										
2	1	3.0	4.5	50		1.0	q	2	0		5.0		4.0					1.0	3.0			B382372	252.98	254.51	0.033			VA05062470	1.53
2	6	0.2	0.4	100		1.0	q/cb	3	0	40.0	20.0							4.0										
							chl	1																				
4	1	1.5	4.5	50		2.0	q/chl	3	0		20.0							1.0				B382373	254.51	256.03	0.026			VA05062470	1.52
							cb	1																				
5	1	2.0	8.0	50		1.0	q/chl	3	0	3.0	5.0		20.0					3.0				B382374	256.03	257.56	0.626			VA05062470	1.53
							cb	1																				
4	1	1.2	4.0	50		1.0	q/chl	2	0													B382375	257.56	259.08	0.027			VA05062470	1.52
							cb	2																				
																						B382376	BLANK		<0.005			VA05062470	
3	6	0.5	1.2	40	120	0.0				100.0								2.0				B382377	259.08	259.90	0.034			VA05062470	0.82
6	6	0.3	2.0	40	90	2.0	b/q	1	0	100.0								4.0				B382378	259.90	260.60	0.062			VA05062470	0.70
1	1	1.5	1.5	40		1.0	q/chl	3	0																			
3	1	1.5	4.0	45	80	2.0	q/cb	3	1				0.1									B382379	260.60	262.13	0.027		qtz veins all rearranged	VA05062470	1.53
							chl	1																				
5	6	0.5	1.8	20	35	5.0	cb	5	2	100.0								4.0										
4	1	1.5	5.5	65	45	0.0							0.1									B382380	262.13	263.04	0.062		bunched' sulph. Veins into 15cm lengths w/in GND texture	VA05062470	0.91
40	6	0.2	35.0	45						90.0	10.0			0.1	0.1			4.0										
3	1	1.0	3.0	120		1.0	q/cb	3	1		5.0		5.0					2.0	4.0			B382381	263.04	263.65	0.018			VA05062470	0.61
							cb	3																				
20	6	0.5	3.0	50			cb	3		100.0								4.0										
3	1	1.0	3.0	120		1.0	q/cb	3	1		5.0		5.0					2.0	4.0			B382382	263.04	263.65	0.036	DUP		VA05062470	0.61
20	6	0.5	3.0	50			cb	3		100.0								4.0										
2	1	1.0	2.0	50		1.0	q	2			5.0		5.0					2.0	4.0			B382383	263.65	264.38	0.061			VA05062470	0.73
4	6	0.2	0.8	50						100.0								4.0										
2	4	0.5	1.0	65		2.0	cb	4		5.0			5.0					5.0	4.0			B382384	264.38	265.18	0.034			VA05062470	0.80
4	1	1.0	3.5	115		2.0	q/cb	3																				
3	4	0.2	0.6	30		0.5	cb	2		5.0								5.0				B382385	265.18	265.99	0.007			VA05062470	0.81
1	1	0.6	0.6	130		1.0	q	3					15.0						4.0										
3	4	0.2	0.6	20	35	1.0	cb	3		5.0								5.0				B382386	265.99	266.57	0.009			VA05062470	0.58
																								E.O.H.				

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-292C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 750m

BEARING: 000 | DIP: -50°

DATE STARTED: 08-Jul-05 | DATE COMPLETED: 10-Jul-05

LOGGED BY: Terry Croteau Jul.8-12, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 458490 NORTHING: 70985567

COORD SYSTEM: NAD 83: EASTING: 458371 NORTHING: 7098567

NAD 27 (CORRECTED for historic grid): EASTING: 458460 NORTHING: 7098577

SECTION LINE(historic grid): 458460

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 1.53m

Deviation:

Casing: 12.19m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B380611 to B380791 (all)

Requisition #: MASP448STRGOL.05Q | Date Shipped: 15-Jul-05

Lab Record #: VA05060561 | Date Received: 22-Jul-05

Duplicates:	B380622, B380642, B380662, B380682, B380702, B380722, B380742, B380762, B380782,
Preparation Duplicate/ Check Assay:	B380629, B380649, B380669, B380689, B380709, B380729, B380749, B380769, B380789,
Standards:	B380630(3C), B380650(4D), B380670(5E), B380690(2B), B380710(5E), B380730(3C), B380749(1A), B380770(4D), B380790(3C)
Blanks:	B380616, B380636, B380656, B380676, B380696, B380716, B380736, B380756, B380776,

LITHOLOGY

FROM	TO	
12.19	202.69	MSED

ALTERATION

FROM	TO	

MINERALIZATION (Veins)

FROM	TO	

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
202.7	346.6	51.9	012.6	013.6
18.3	340.0	47.3	006.0	007.0
100.6	344.3	49.0	010.3	011.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1 | DATE: July 8 = 10th, 2005 | PAGE 1 of 8

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-12.19			CASING						
1	12.19-13.72			OVB: Core is broken, 70% rounded pebbles of qtz, QZZ, MSED, + other detrital material. Likely from drilling on washed gravel pile. Poor recovery.						
70	13.72-25.91			QZZ: 90% qtz, 5% k-feld, 3% bt, ±2% sulphides						
70		13.72	15.24	Core is broken. Silicous, lim staining on fract faces. Some fracture faces have clay on surface. Fractures are filled w/ sulphides py, aspy. Diss py and aspy can also be found. At 14.94m, a- 30cm qtz vein. Unable to determine angle or contact. Light grey colour, fractures ox'd, tr py.	1			1		
70		15.24	19.81	Core becomes more broken, still highly silicious. Less lim on frac faces. Veinlets of sulphides, also fracture fill, and small (<1mm) euhedral py crystals on frac faces.	1					
70		19.81	21.34	Fracture are heavily stained by lim. Minor ser can be found on a few (5%) of frac faces. Py and aspy fill irregular fractures. Also found as diss sulphides	2	1				
70		21.34	25.91	Core is broken into mostly (80%) gravel to cobble size pieces. Minor lim staining on pebbles from 22.86 to 23.10m. Minor clay on frac surfaces. Diss py found throughout.	1			1		
70		25.91	27.43	Core is dark grey, still. Silicious, minor lim staining, no clay.						
80	27.43-38.10	27.43	28.13	MSED. Core is dark grey to black, fine gr. Qtz eyes and lenses are present. Black colour is due to graphite. Foliation present, but no preferred orientation, instead "s". Possible fault (looks similar to 287C). Diss py on faces (1%).						
80		28.13	28.96	Core is light grey, with white laminae. Silicious with ser on faces. Foliations at 40° to CA. At 28.73m, 23cm clay gouge contains MSED frags.		2		3		
80		28.96	33.53	Bleached, silicified MSED. Core is a light tan colour. Foliation often difficult to distinguish, overprinted. Where visible it ranges from 65-75°. Chl common on fractures, as is ser and clay.		2	2	2		
80		33.53	38.10	Core is less silicious. Chl alt'n more intense, ser and clay alt'n is reduced. Foliation at 45-50°.		1	3	1		
81	38.10	38.10	48.77	HFLS: Core is foliated. Colour is banded brown, violet and green. Foliation is at 50° to CA until 42.87m, where it is at 70°to CA. It returns to 50-60° at 49.20m. Very few qtz veins or sulphides are present. Fractures are filled with chl, ser, and minor carb. Frac faces show the same. The qtz veins that do exist run parallel to foliation. At 43.04m, 2cm clay gouge. Core on either side shows slickensides. Core is soft, easy to scratch - chl.		2	2	1	1	
80	48.77-49.37	48.77	49.37	HFLS giving way to more silicious MSED. Foliations no longer visible. Increase in carb veinlets. Trace py on fractures.		1	1		2	
81	49.37-56.39	49.37	56.39	HFLS - Similar to HFLS at 38.10m, with more intense clay and chl alteration. Frequent areas of gouge. Foliation at 50-55° from 49.37 to 53.43m, at 60-65° from 53.43 to 56.39m. At 51.52m, 3cm gouge at 45° to CA. At 53.04m, 6cm clay gouge at 70° to CA. At 54.52m, 4cm gouge at 70° to CA.		1	3	3	1	
80	56.39-59.44	56.39	59.44	MSED - Silicified, difficult to scratch. No visible foliation. Minor ser on frac.		1		1	1	
81	59.44-62.48	59.44	61.56	HFLS. Foliation at 80°, minor clay alt'n.		1	2	1	1	
81		61.56	62.48	HFLS heavily alt'd to clay (80%). Small fragments of HFLS found within		1	2	4	1	
80	62.48-64.71	62.48	64.71	MSED - Silicious MSEDs. Foliation is difficult to distinguish: From 62.48-64.01m, @80° to CA; From 64.01-64.71m, @50° to CA. At 62.75m, 10cm trace py on frac faces w/ slickensides.		1	1	1		
81	64.71-65.53	64.71	65.53	HFLS. Chl and clay on fracs. Foliation at 80°, crenulations		2	2	1	1	
80	65.53-67.06	65.53	67.06	Silicious MSED. Black, with white, 1mm bands at 85° to CA. Contact with hornfels at 70°		1	1	1		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B380611	12.19	13.72	0.006			VA05060561	1.53
2	1	30.0								1.0												B380612	13.72	15.24	0.041		no vein contacts. veins are broken, or in pieces.	VA05060561	1.52
	4																					B380613	15.24	16.76	0.137			VA05060561	1.52
2	6	0.1	0.2	65									1.0					10.0				B380614	16.76	18.29	0.025			VA05060561	1.53
3	6	0.1	0.3	65						1.0								10.0				B380615	18.29	19.81	0.113			VA05060561	1.52
																						B380616	BLANK		<0.005			VA05060561	
3	6	0.1	0.3	65						1.0			1.0									B380617	19.81	22.86	0.025		B380617 is 3m sample; Tag B380618 was misplaced.	VA05060561	3.05
2	1	0.5	0.7	50						1.0			1.0									B380619	22.86	24.38	0.011			VA05060561	1.52
4	1	0.2	0.8	50						0.1												B380620	24.38	25.91	0.084			VA05060561	1.53
2	6	0.2	0.4	50						1.0			1.0									B380621	25.91	27.43	0.012			VA05060561	1.52
2	6	0.2	0.4	50						1.0			1.0									B380622	25.91	27.43	0.012	DUP		VA05060561	1.52
0																						B380623	27.43	28.13	0.009			VA05060561	0.70
0																						B380624	28.13	28.96	<0.005			VA05060561	0.83
2	3			15																		B380625	28.96	30.48	<0.005		veinlets	VA05060561	1.52
7	3			15																		B380626	30.48	32.00	<0.005		veinlets	VA05060561	1.52
0																						B380627	32.00	33.53	<0.005			VA05060561	1.53
																						B380628	33.53	35.05	<0.005			VA05060561	1.52
																						B380629	33.53	35.05	<0.005	PD/CA		VA05060561	1.52
																						B380630	STANDARD 3C		0.088	3C		VA05060561	
2	1	0.2	0.4	40	175								0.1									B380631	35.05	36.58	0.007			VA05060561	1.53
5	1	1.0	1.6	50						2.0												B380632	36.58	38.10	<0.005			VA05060561	1.52
	4																					B380633	38.10	39.62	<0.005		veinlets at same orientation as foliation	VA05060561	1.52
1	1	7.0	7.0	55		2	chl	4	0	0.1												B380634	39.62	41.15	0.006			VA05060561	1.53
	4																					B380635	41.15	42.67	<0.005		veinlets at same orientation as foliation	VA05060561	1.52
																						B380636	BLANK		<0.005			VA05060561	
1	1	1.0	1.0	50						1.0												B380637	42.67	44.20	<0.005		vein between foliation	VA05060561	1.53
1	4	0.2	0.2	35																		B380638	44.20	45.72	<0.005			VA05060561	1.52
	4			35																		B380639	45.72	47.24	<0.005		carb veinlets	VA05060561	1.52
2	1	0.2	0.4	50							0.1											B380640	47.24	48.77	<0.005			VA05060561	1.53
3	1	1.0	1.4	85	145						0.0											B380641	48.77	49.37	0.008		veins at 145°crosscut foliation	VA05060561	0.60
3	1	1.0	1.4	85	145						0.0											B380642	48.77	49.37	0.006	DUP		VA05060561	0.60
	4			40	50																	B380643	49.37	50.29	<0.005		carb veinlets	VA05060561	0.92
	4			45	55																	B380644	50.29	51.82	0.005		carb veinlets	VA05060561	1.53
1	1																					B380645	51.82	53.34	<0.005		irregular fracture fill	VA05060561	1.52
1	1	3.0	3.0	85						1.0												B380646	53.34	54.86	<0.005		py in tension gashes	VA05060561	1.52
0																						B380647	54.86	56.39	<0.005			VA05060561	1.53
	4			5	10																	B380648	56.39	57.91	0.007			VA05060561	1.52
	4			5	10																	B380649	56.39	57.91	<0.005	PD/CA		VA05060561	1.52
																						B380650	STANDARD 4D		0.431	4D		VA05060561	
	4			80																		B380651	57.91	59.44	<0.005		carb veinlets	VA05060561	1.53
				80																		B380652	59.44	60.91	<0.005		carb veinlets	VA05060561	1.47
																						B380653	60.91	61.56	<0.005			VA05060561	0.65
0																						B380654	61.56	62.48	<0.005			VA05060561	0.92
	4			30	130																	B380655	62.48	64.01	<0.005		carb veinlets	VA05060561	1.53
																						B380656	BLANK		<0.005			VA05060561	
	4			30																		B380657	64.01	64.71	<0.005		carb veinlets	VA05060561	0.70
	4			80																		B380658	64.71	65.53	<0.005		carb veinlets	VA05060561	0.82
	4			45	80																	B380659	65.53	67.06	0.010			VA05060561	1.53

DRILL LOG LEGEND P1

DATE: July 8 = 10th, 2005 PAGE 3 of 8

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81	67.06-70.98	67.06	70.98	HFLS. Foliation at 85-90° to CA. Qtz intrudes between foliations at 69.72m and contain 1% py. Chl and ser on frac faces.		2	2	1	1	
80	70.98-73.15	70.98	73.15	Silicious MSED. No visible foliation. Increase in veining, with minor sulphides. Core is black with green bands. Frac faces @72.70m show py on them. Contact w/ hornfels at 70°						
81	73.15-81.80	73.15	74.68	Foliation at 80° to CA. At 73.40m, 6cm grey qtz vein, at 80° to CA, trace py. At 73.97m, silicified MSED, ser on frac's.		2	2	1		
81		74.68	76.20	Very poor recovery (16%), pieces of qtz vein (3-5cm) and HFLS. At 76.18m, 2cm gouge, sandy.						
81		76.20	81.80	HFLS. Foliation at 60°. Qtz intrudes foliation or crosscuts. Chl content increases after 79.25m. At 79.25m, foliation becomes 70-75°. At 81.32m, foliation at 80-85°.		2	3	1	1	
80	81.80-82.30	81.80	82.30	Silicious MSED. Fractures filled w/ carb light grey colour. Py on frac surface (tr.). At 82.10m, 3cm sandy gouge at 40°. Contact w/ HFLS to 80°.				1	2	
81	82.30-83.72	82.30	83.72	HFLS. Foliation @ 75-80°. Slightly more clay alt'n. At 82.73m, 5cm grey qtz vein @90° to CA.						
80	83.72-85.15	83.72	85.15	Silicious MSED w/ interbedded HFLS. Foliation only visible in the HFLS at 80-85° to CA. Tr py on MSED frac faces.		1	2	1		
81	85.15-87.43	85.15	86.56	HFLS. Foliation @ 80-85° to CA. Core has a slight green tinge to it - chl dominant alt'n. Minor ser and clay on frac. Smells like sulphur when scratched - minor sphalerite		1	3	2		
		86.56	86.87	~20cm grey qtz vein, broken, no visible contacts. 15-20% massive sulphides: py + aspy						
		86.87	87.43	Broken pieces of qtz vein w/ py and aspy as massive sulphides. Also pieces of silicified MSED.						
80	87.43-91.44	87.43	91.44	MSED. Silicified, no visible foliation or contact. Tan coloured clay on frac surfaces.				1		
81	91.44-92.96	91.44	92.96	HFLS. Foliation @ 75-80°. Qtz veins intrude foliation. Carb veinlets follow foliation at 75-80°		1	3	2		
80	92.96-94.86	92.96	94.86	Silicified MSED. Foliation difficult to see, but @ 45-50° where visible. At 93.16m, 7cm grey qtz vein. Bismuthinite on frac face.						
81	94.86-101.88	94.86	101.88	HFLS. Foliation at 94.86m at 70°, at 96.01m, 75-80°, at 97.56m, 55-60°, at 99.06m, 55-60°, at 100.56m, 60-65°. Clay and chl alt'n common. Cb veinlets abundant.		1	3	2	1	
80	101.88-105.16	101.88	105.16	MSED. Silicified, foliation @ 101.81m - 85-90°, @102.11m - 70-75°, @103.63m - 75-80°. Foliation is difficult to distinguish due to overprinting. At 104.08m, 8cm tan coloured sandy gouge. MSED frags present.		1	2	2		
81	105.16-111.25	105.16	107.20	Silicified HFLS. Does not scratch easily. Less chl and ser alt'n. Violet and green colour. Foliation at 60°.		1	1	1		
81		107.20	111.25	HFLS. Easy to scratch, higher chl content - more green banding. Foliation @ 107.2m - 80°, @108.20m, 90-95° - crenulated for 9cm. After this, @110°. @109.73m - 110°. @110.33, 4cm clay gouge @80° to CA. @110.82m, 5cm clay gouge @70° to CA.		2	2	2	1	
80	111.25-114.30	111.25	114.30	Silicified MSEDS. Foliation visible: @111.25m, 60-65°. @112.78m, 70-75°. @111.99m, 10 cm qtz vein grey qtz @80° to CA. Contains 1% po. Diss py present, also intrudes foliation.		1	1	1		
81	114.30-115.54	114.30	115.54	HFLS. Easily scratched by nail. Foliation @60-65° to CA. Chl on frac faces. Carb veins return, crosscut foliation		1	3	2	1	
80	115.54-116.50	115.54	116.50	Silicious MSED. Light grey color. Carb on frac faces. Foliations @ 75-80° to CA					1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
	1																					B380660	67.06	68.58	<0.005		qtz intrudes foliation	VA05060561	1.52
2	1	1.0	1.2	60						1.0												B380661	68.58	70.10	<0.005			VA05060561	1.52
2	1	1.0	1.2	60						1.0												B380662	68.58	70.10	<0.005	DUP		VA05060561	1.52
1	1	1.0	1.0	70																		B380663	70.10	70.98	<0.005		no visible sulphides	VA05060561	0.88
5	4	0.1	0.5	35																		B380664	70.98	71.63	<0.005			VA05060561	0.65
																						B380665	71.63	73.15	<0.005			VA05060561	1.52
1	1	5.0	5.0	50						0.1												B380666	73.15	74.68	<0.005			VA05060561	1.53
1	1	5.0								0.1												B380667	74.68	76.20	0.015		broken into pieces, may be larger than 5cm	VA05060561	1.52
3	1	2.0	6.0	60						0.1												B380668	76.20	77.22	<0.005			VA05060561	1.02
3	1	2.0	6.0	60						0.1												B380669	76.20	77.22	<0.005	PD/CA		VA05060561	1.02
																						B380670	STANDARD 5E		1.505	5E		VA05060561	
2	1	0.5	1.0																			B380671	77.72	79.25	<0.005		veins irregular	VA05060561	1.53
2	1	0.5	1.0																			B380672	79.25	80.77	<0.005		veins irregular	VA05060561	1.52
0																						B380673	80.77	81.80	<0.005			VA05060561	1.03
7	4	0.2	1.4	20																		B380674	81.80	82.30	<0.005		carb veinlets	VA05060561	0.50
1	1	5.0	5.0	90							1.0											B380675	82.30	83.72	<0.005			VA05060561	1.42
																						B380676	BLANK		<0.005			VA05060561	
4	1	2.0	3.0	85							0.1											B380677	83.72	85.15	<0.005		veins irregular; only 1 at 85°	VA05060561	1.43
2	1	0.2	0.4																			B380678	85.15	86.56	<0.005		irregular, intrude between foliations	VA05060561	1.41
1	1	20.0	20.0							20.0			15.0									B380679	86.56	86.87	0.280			VA05060561	0.31
1	1									10.0			10.0									B380680	86.87	87.43	0.014		broken into gravel size pieces	VA05060561	0.56
2	1	1.5	1.7	80		8	5	4		1.0												B380681	87.43	88.39	<0.005			VA05060561	0.96
2	1	1.5	1.7	80		8	5	4		1.0												B380682	87.43	88.39	<0.005	DUP		VA05060561	0.96
	4			25																		B380683	88.39	89.92	0.005		cb veinlets	VA05060561	1.53
	4			30																		B380684	89.92	91.44	<0.005		cb veinlets	VA05060561	1.52
	4			60	20																	B380685	91.44	92.96	<0.005		cb veinlets	VA05060561	1.52
1	1	7.0	7.0			15	q	4	0	0.1												B380686	92.96	94.49	<0.005		bismuthinite on frac face	VA05060561	1.53
1	1	0.5	0.5	80																		B380687	94.49	94.86	<0.005			VA05060561	0.37
	4			60																		B380688	94.86	96.01	<0.005		cb veinlets	VA05060561	1.15
	4			60																		B380689	94.86	96.01	<0.005	PD/CA		VA05060561	1.15
																						B380690	STANDARD 2B		3.290	2B		VA05060561	
	4			50																		B380691	96.01	97.56	<0.005		cb veinlets	VA05060561	1.55
0																						B380692	97.56	99.06	0.012			VA05060561	1.50
0																						B380693	99.06	100.58	<0.005			VA05060561	1.52
0																						B380694	100.58	101.88	<0.005			VA05060561	1.30
2	1	0.5	1.0																			B380695	101.88	102.11	<0.005		pieces, unable to attain orientation	VA05060561	0.23
																						B380696	BLANK		<0.005			VA05060561	
1	1	1.0	1.0	85																		B380697	102.11	103.63	0.008			VA05060561	1.52
	2			60																		B380698	103.63	105.16	<0.005		veinlets	VA05060561	1.53
	2			60																		B380699	105.16	106.68	<0.005		veinlets	VA05060561	1.52
1	1	5.0	5.0	40						1.0												B380700	106.68	107.20	0.010		irregular shape	VA05060561	0.52
	2			65																		B380701	107.20	108.20	<0.005		veinlets	VA05060561	1.00
																						B380702	107.20	108.20	<0.005	DUP		VA05060561	1.00
1	1	2.0	2.0	70		2	chl	5	0	0.1												B380703	108.20	109.73	<0.005			VA05060561	1.53
	2	25.0																				B380704	109.73	111.25	0.005		veinlets	VA05060561	1.52
1	1	1.0	1.0	90																		B380705	111.25	111.99	<0.005			VA05060561	0.74
1	1	10.0	10.0	85		3	chl	4	0		1.0											B380706	111.99	112.17	<0.005			VA05060561	0.18
	2			25																		B380707	112.17	112.78	<0.005		veinlets	VA05060561	0.61
	2			30	175																	B380708	112.78	114.30	<0.005		veinlets	VA05060561	1.52
																						B380709	112.78	114.30	<0.005	PD/CA		VA05060561	1.52
																						B380710	STANDARD 5E		1.475	5E		VA05060561	
2	4	0.1	0.2	50																		B380711	114.30	115.54	<0.005			VA05060561	1.24
	2			80																							veinlets		
	2			170																		B380712	115.54	116.50	0.021		veinlets	VA05060561	0.96

DRILL HOLE # : DG05-292C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81	116.50-117.35	116.50	117.35	HFLS. Soft, easily scratchable. Foliation @ 70-75° to CA. Chl alt'n dominant.		1	2	2	1	
80	117.35-118.87	117.35	118.87	Silicious MSED. Dark grey, banded. Foliation @ 70-75°.						
81	118.87-123.44	118.87	123.44	HFLS and silicious MSED, interbedded. Foliation @119.07m - 45-50°, @120.90m - 70-75°; @ 121.92m - 60-65°. The HFLS has lower angle foliation than the MSED.		1	2	1	1	
80	123.44-202.69	123.44	125.83	MSED. Chloritized with several large (> 5cm) qtz veins. Carb on frac faces and in veinlets. Some veins are irregular, some follow foliation. @123.49m, 8cm grey qtz vein @ 65° to CA @124.47m, 8cm grey qtz vein @ 75° to CA, tr py @124.73m, 10cm qtz vein @40° to CA, 1% po			3		2	
80		125.83	134.11	Foliation @ 125.83m - 55-60°, @126.49m - 55-60°, @128.02m - 55-60°, @129.59m - 70-75°, @131.06m - 75-80°, @132.59m - 85-90° to CA. Cb veinlets crosscut foliation as do sulphides, which are rare containing only trace amounts.		1	2	1	1	
80		134.11	147.83	MSED Silicious, dark brown to dark grey. Most qtz veins run between foliations. Some are irregular shape, as well as filled gashes. Foliation @134.11m - 85-90°, @135.64m - 85-90°, @137.16m - 85-90° - aspy crystals on frac faces @138.68m - 85-90° @140.24m - 75-80° @141.73m - 65-70° @143.26m - 70-75° - diss po and cpy @144.78m - 70-75° - diss po and cpy @146.30m - 65-70° - diss po and cpy There is an increase in shear over this interval. Boudins are present starting at 144.78m and continuing until 154.85m.		2			1	
80		147.83	149.35	Core is light green, contains abundant ser, chl. Trace diss po present.		2	2	1		
80		149.35	154.85	MSED Grey green to grey. Shear is highly visible as boudins. Foliation @149.35m - 55-60° @150.88m - 45-50° @152.40m - 65-70° @153.92m - 65-70° Qtz fills gashes, crosscutting foliation or follows foliation or crenulation. Diss py occurs from 149.35 - 152.40m in darker core. Diss aspy occurs from 152.40-154.85m in lighter coloured core		2	2	1	1	
80		154.85	158.50	Core is light green to white. Ser alt'n. Veining increases, filling gashes and between foliation. Carb alt'n increases. Foliation @ 65 - 70° to CA. Shearing indicators absent.		3	1		2	
80		158.50	161.54	Silicified MSEDS. Foliation is difficult to distinguish, most has been overprinted. Dissem aspy, vnlets and euhedral crystals on frac face. Foliation (where visible) @ 50-55°.						
80		161.54	175.26	MSED and HFLS interbedded. Boudins present--increased shear. Carb alt'n increased. Foliations at: 161.54m--60-65°; 163.07m--65-70° (7cm qtz vn @163.82m); 164.59m--65-70° (8cm qtz vn @ 165.21m); 166.12m--60-65°; 167.64m--65-70°; 169.16m--60-65°; 170.69m--75-80°; 172.21m--55-60°; 173.74m--60-65°. Qtz vns follow foliation. Trace dissem py present. Sulphide content increased compared to other intervals.		2	2	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	75																		B380713	116.50	117.35	0.007			VA05060561	0.85
	4			170																		B380714	117.35	118.87	<0.005		veinlets	VA05060561	1.52
2	3	0.2	0.4	50	162																	B380715	118.87	120.40	<0.005			VA05060561	1.53
																						B380716	BLANK		<0.005			VA05060561	
2	4	0.2	0.4	55																		B380717	120.40	121.92	<0.005		veinlets	VA05060561	
2	1	4.0	6.0	45	65					0.1												B380718	121.92	123.44	<0.005			VA05060561	1.52
3	1	11.0	26.0	40	75					0.1	1.0											B380719	123.44	124.97	<0.005			VA05060561	1.53
3				170																		B380720	124.97	125.83	<0.005		veinlets	VA05060561	0.86
3	1	0.2	0.6	70							0.1											B380721	125.83	126.49	<0.005			VA05060561	0.66
3	1	0.2	0.6	70							0.1											B380722	125.83	126.49	<0.005	DUP		VA05060561	0.66
3	1	0.2	0.6	80							0.1											B380723	126.49	128.02	<0.005			VA05060561	1.53
2	1	1.0	1.5	60																		B380724	128.02	129.59	<0.005			VA05060561	1.57
	4			50																		B380725	129.59	131.06	<0.005		veinlets	VA05060561	1.47
	4			55																		B380726	131.06	132.59	<0.005		veinlets	VA05060561	1.53
	4			50																		B380727	132.59	134.11	<0.005		veinlets	VA05060561	1.52
2	1	2.0	3.0	80																		B380728	134.11	135.64	<0.005			VA05060561	1.53
2	1	2.0	3.0	80																		B380729	134.11	135.64	0.005	PD/CA		VA05060561	1.53
																						B380730	STANDARD 3C		0.092	3C		VA05060561	
	2			30																		B380731	135.64	137.16	<0.005		veinlets	VA05060561	1.52
	1																					B380732	137.16	138.68	<0.005		irregular fill/gashes	VA05060561	1.52
1	1	1.0	1.0	50																		B380733	138.68	140.24	<0.005			VA05060561	1.56
1	6	0.1	0.1	160						0.1								95.0				B380734	140.24	141.73	0.007			VA05060561	1.49
1	1	1.0	1.0	50							1.0											B380735	141.73	143.26	<0.005			VA05060561	1.53
																						B380736	BLANK		<0.005			VA05060561	
2	3	0.5	1.0	30																		B380737	143.26	144.78	0.617		Diss po and cpy	VA05060561	
1	1	0.5	0.5	70																		B380738	144.78	146.30	<0.005		Diss po and cpy	VA05060561	1.52
3	6	0.1	0.3	160						0.1								95.0				B380739	146.30	147.83	<0.005			VA05060561	1.53
1	3	0.5	0.5	10																		B380740	147.83	149.35	<0.005			VA05060561	1.52
1	1	5.0	5.0	55						0.1												B380741	149.35	150.88	0.005			VA05060561	1.53
1	1	5.0	5.0	55						0.1												B380742	149.35	150.88	0.007	DUP		VA05060561	1.53
2	3	0.1	0.2	30																		B380743	150.88	152.40	0.008			VA05060561	1.52
1	1	2.0	2.0	60						1.0												B380744	152.40	153.92	<0.005			VA05060561	1.52
5	1	2.0	3.0	60																		B380745	153.92	154.85	<0.005			VA05060561	0.93
	1	0.5																				B380746	154.85	155.40	<0.005		filled gashes	VA05060561	0.55
5	1	3.0	6.0	70																		B380747	155.40	156.97	<0.005			VA05060561	1.57
0																						B380748	156.97	158.50	0.010			VA05060561	1.53
																						B380749	156.97	158.50	0.009	PD/CA		VA05060561	1.53
																						B380750	STANDARD 1A		0.871	1A		VA05060561	
6	6	0.1	0.6	30						1.0								70.0				B380751	158.50	160.02	<0.005			VA05060561	1.52
2	3	0.2	0.4	25																		B380752	160.02	161.54	0.011			VA05060561	1.52
3	3	0.2	0.6	27																		B380753	161.54	163.07	<0.005			VA05060561	1.53
5	1	7.0	15.0	80						1.0				2.0								B380754	163.07	164.59	0.005			VA05060561	1.52
2	1	8.0	9.0	85						0.1												B380755	164.59	166.12	<0.005			VA05060561	1.53
																						B380756	BLANK		<0.005			VA05060561	

DRILL LOG LEGEND P1

DATE: July 8 = 10th, 2005 PAGE 7 of 8

DRILL HOLE # : DG05-292C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		175.26	181.36	Silicified MSED. Light grey green color. Foliation is difficult to see, when foliation is visible boudins present. Foliations at: 175.26m--55-60°; 176.68m--55-60°; 178.31m--45-50°; 179.83m--45-50°. Dissem aspy present @ 176.78m-178.31m. At 178.56m: 15cm sandy texture-ss. Increase in carb vning.		1	1		1	
80		181.36	182.88	Dark grey MSED. Boudins still present-shear. Frac faces show chl. Foliation @ 65-70° to CA.		2	2	1	1	
80		182.88	185.03	MSED are light grey and silicified, boudins are reduced, possibly overprinted. Foliation is difficult to see. Foliation @: 182.88m--80-85°; 184.40m--85-90°. Vns btwn foliations.						
80		185.03	185.60	MSED dark grey, boudins again visible. Foliation @ 80-85°. Qtz vns btwn foliations.		2	2		1	
80		185.60	185.85	25cm white qtz vn @ 60° to CA. Trace py and aspy.						
80		185.85	186.65	Silicified MSED. Carb on frac faces, boudins present-shear. Foliation overprinted, but where visible @ 85° to CA. Qtz vns crosscut foliation, and run parallel. Light grey color, large number of qtz vns (10).			1		2	
80		186.65	188.98	Dark grey MSED. Soft, easily scratched. Boudins present w/ dissem aspy. Qtz vns less common. Foliation @ 85-90°.		2	2		1	
80		188.98	193.55	Dark grey MSED. Harder to scratch, silicious. Very little foliation is visible @ 75-80°. Trace cb on frac faces, boudins visible where foliation visible.			1		1	
80		193.55	194.47	Easily scratchable, green to grey color. Chl on frac faces, foliation @ 65° to CA.		2	2		1	
80		194.47	195.07	Core is light grey green, silicious. No visible foliation.						
80		195.07	202.69	MSED, soft, easily scratchable. Colour varies from green to grey. Boudins visible throughout section. Foliation @: 195.07m--75-80°; 196.60m--55-60° (dissem aspy); 198.12m--55-60°; 199.69m--85-90°; 201.17m--65-70°. Vns follow foliation, most have irregular shape.						
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8 - 10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Interval Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
2	1	1.0	1.5	60																		B380757	166.12	167.64	<0.005			VA05060561	1.52
5	6	0.1	0.5	5	10								2.0									B380758	167.64	169.16	<0.005			VA05060561	1.52
3	1	0.5	0.9	65																		B380759	169.16	170.69	0.008			VA05060561	1.53
3	1	1.0	1.4	60									0.1									B380760	170.69	172.21	<0.005			VA05060561	1.52
2	3	0.5	1.0	7																									
2	3	0.5	1.0	10																		B380761	172.21	173.74	<0.005			VA05060561	1.53
2	3	0.5	1.0	10																		B380762	172.21	173.74	<0.005	DUP		VA05060561	1.53
	3			10																		B380763	173.74	175.26	<0.005		vnlets	VA05060561	1.52
1	1	6.0	6.0	70						1.0												B380764	175.26	176.78	<0.005			VA05060561	1.52
4	1	1.5	3.0	40	70					1.0			0.1									B380765	176.78	178.31	0.017			VA05060561	1.53
3	1	1.5	3.0	45						0.1												B380766	178.31	179.83	0.005			VA05060561	1.52
1	6	0.2	0.2	35						3.0								10.0											
1	1	2.0	2.0	65						0.1												B380767	179.83	181.36	0.005			VA05060561	1.53
1	1	2.0	2.0	70																		B380768	181.36	182.88	0.022			VA05060561	1.52
1	1	2.0	2.0	70																		B380769	181.36	182.88	0.023	PD/CA		VA05060561	1.52
																						B380770	STANDARD 4D		0.429	4D		VA05060561	
4	1	9.0	12.0	65						1.0												B380771	182.88	184.40	0.011			VA05060561	1.52
5	1	3.0	11.0	65						1.0												B380772	184.40	185.03	<0.005			VA05060561	0.63
4	1	4.5	9.0	65						0.1												B380773	185.03	185.60	<0.005			VA05060561	0.57
1	1	25.0	25.0	60						0.1			0.1									B380774	185.60	185.85	<0.005			VA05060561	0.25
11	1	5.0	15.0	60						0.1			0.1									B380775	185.85	186.65	<0.005			VA05060561	0.80
																						B380776	BLANK		<0.005			VA05060561	
1	1	3.0	3.0	75																		B380777	186.65	187.45	<0.005			VA05060561	0.80
2	1	3.0	3.0	85						0.1												B380778	187.45	188.98	0.006			VA05060561	1.53
3	1	1.0	3.0	85	80								0.1									B380779	188.98	190.50	0.005			VA05060561	1.52
8	1	2.0	6.0	80						0.1												B380780	190.50	192.02	0.005			VA05060561	1.52
2	2	0.2	0.4	75						0.1			0.1									B380781	192.02	193.55	0.035			VA05060561	1.53
2	2	0.2	0.4	75						0.1			0.1									B380782	192.02	193.55	0.025	DUP		VA05060561	1.53
4	1	2.0	5.0	75									0.1									B380783	193.55	194.47	<0.005			VA05060561	0.92
3	6	0.1	0.3	15						1.0																			
2	1	0.2	0.4	75									0.1									B380784	194.47	195.07	0.008			VA05060561	0.60
3	1	1.0	1.4	80									0.1									B380785	195.07	196.60	<0.005			VA05060561	1.53
1	6	0.2	0.2	50						3.0												B380786	196.60	198.12	<0.005			VA05060561	1.52
3	1	1.0	2.0	55									0.1						95.0			B380787	198.12	199.69	<0.005			VA05060561	1.57
1	3	0.2	0.2	30																		B380788	199.69	201.17	<0.005			VA05060561	1.48
1	3	0.2	0.2	30																		B380789	199.69	201.17	0.005	PD/CA		VA05060561	1.48
																						B380790	STANDARD 3C		0.092	3C		VA05060561	
4	1	1.0	2.5	75							0.1											B380791	201.17	202.69	<0.005			VA05060561	1.52
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-293C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 762m

BEARING: 000 | DIP: -50°

DATE STARTED: 11-Jul-05 | DATE COMPLETED: 14-Jul-05

LOGGED BY: Terry Croteau July 13-16, 2005

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 458456 NORTHING: 7098452

COORD SYSTEM: NAD 83: EASTING: 458337 NORTHING: 7098635

NAD 27 (CORRECTED for historic grid): EASTING: 458426 NORTHING: 7098462

SECTION LINE(historic grid): 458426E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 15.24m

Deviation:

Casing: 18.29m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B380792-B380836

Requisition #: MASP448STRGOL.05Q Date Shipped: 15-Jul-05

Lab Record #: VA05060560 Date Received: 22-Jul-05

Sample Sequence: B380837-B380922

Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05

Lab Record #: VA05062472 Date Received: 27-Jul-05

Duplicates:	B380802; B380822; B380842; B380862; B380882; B380902; B380922
Preparation Duplicate/ Check Assay:	B380809; B380829; B380849; B380869; B380889; B380909
Standards:	B380810 (6F); B380830 (2B); B380850 (4D); B380870 (5E); B380890 (7G); B380910 (3C)
Blanks:	B380796; B380816; B380836; B380856; B380876; B380896; B380916

FROM	TO	LITHOLOGY
15.24	19.81	OVB
19.81	21.34	QZZ
21.34	22.86	OVB
22.86	36.58	QZZ
36.58	59.44	MSED
59.44	60.96	OVB (contamination?)
60.96	102.28	MSED
102.28	103.63	DIOR (mafic intrusive)
103.63	166.12	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
103.63	338.7	48.9	004.7	005.7
134.11	344.4	49.0	010.4	011.4
166.12	340.8	50.4	006.8	007.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1

DRILL HOLE # : DG05-293C

DATE: July 8-10, 2005 PAGE 1 of 6

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-15.24	0.00	15.24	Casing. 1% recovery, lim on MSED.						
1	15.24-19.81	15.24	16.76	Very poor recovery. 10cm of QZZ, lim stained.						
1		16.76	18.29	Sand, gravel, pebbles. Diverse lithology, likely bedload from creek.	3			1		
1		18.29	19.81	Diverse lithology, core is composed of rounded section of boulders/float, bedload. Lim pervasive & staining.	2					
90	19.81-21.34	19.81	21.34	Broken QZZ. Lim staining on faces. Trace dissem aspy found on faces.	2					
1	21.34-22.86	21.34	22.86	Rounded pebbles-cobbles of diverse lithology mixed w/ broken QZZ & MSEDs. Lim staining on faces. Foliation where visible @ 50-55°.	2					
90	22.86-36.58	22.86	35.05	Broken QZZ w/ lim staining on frac faces. Foliation where visible 55-60°. At 24.38-28.96m: dissem py & aspy. @ 27.83m: Euhedral aspy on faces. @ 28.89m: 7cm sandy gouge. No contact angles.	2					
90		35.05	36.58	QZZ--minor lim staining, absent by end of interval.	1					
80	36.58-59.44	36.58	48.23	Silicious MSED. Colour is light to dark grey, core is broken. Foliations @36.58m: 60-65°- diss aspy; @38.10m: 65-70°- diss aspy; @39.62m: 60-65°- diss aspy; @ 42.67m: 50-55°; @ 44.20m: 55-60°; @ 45.72m: 55-60°; @ 47.24m: 55-60° - diss aspy. Very few vns in section, sulphides mostly dissem or found as euhedral crystals on frac faces.						
80		48.23	55.46	Silicious MSED. Colour varies from light to dark grey. Lim staining returns on faces. Foliation @ 48.23m: 60-65°; @ 48.77m: 65-70°--py on frac face; @ 50.29m: no visible foliations; @ 51.83m: 65-70°; @ 53.36m: no visible foliation; @ 54.86m: no visible foliation--diss py.	2					
80		55.46	56.39	Core is light grey green, heavily lim stained, easily scratchable, no visible foliation.						
80		56.39	57.91	Light brown to light grey MSED. Fracs are filled w/ ox'd py, filling 3% of core. The fracs & vnlets crosscut, as well as follow the foliation. There is no preferred angle (high or low). Foliation @ 55-60°, lim on frac faces.	2	1			1	
80		57.91	59.44	Silicified MSED. Light to dark grey. Foliation @ 55-60°. Low angle (165-170°) carb vns crosscut foliation. Lim on frac faces.	2	1			1	
1	59.44-60.96	59.44	60.96	Broken, rounded pc's of diverse lithology. Possibly came from higher in hole.	2	1	1	1	1	
80	60.96-102.28	60.96	65.00	Light grey MSED. Core is broken, and frac faces covered w/ lim. Foliation @ 60.96m: 55-60°; @ 62.48m: 55-60°; @ 64.01m: 35-40°; @ 64.21m: 45-50°. at 63.31m: 22cm of breccia. Foliation uphole @ 35-40°, downhole @ 55-60°. Contact angles uphole @ 60°, downhole @ 30°. Clasts range from light grey to dark grey MSEDs & qtz. Foliation still visible in MSED clasts. Clast movement may indicate a normal fault (HW uphole), at a high angle ~80°, crosscuts foliation.	2	1				

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8-10th, 2005

LOGGED BY: Terry Croteau

PAGE 2 of 6

094876

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
0																						B380792	15.24	16.76	<0.005			VA05060560	1.52
0																						B380793	16.76	18.29	0.241			VA05060560	1.53
1	1	3.0	3.0	90																		B380794	18.29	19.81	0.165			VA05060560	1.52
1	1	3.0	3.0	90																		B380795	19.81	21.34	0.174			VA05060560	1.53
																						B380796	BLANK		<0.005			VA05060560	
0																						B380797	21.34	22.86	0.090			VA05060560	1.52
1	6	0.1											0.1									B380798	22.86	24.38	0.021		broken into pc's	VA05060560	1.52
0																						B380799	24.38	25.91	0.019		dissem aspy	VA05060560	1.53
3	6	0.1								0.1												B380800	25.91	27.43	0.374		dissem aspy	VA05060560	1.52
2	6	0.2	0.4										1.0									B380801	27.43	28.96	0.845			VA05060560	1.53
2	6	0.2	0.4										1.0									B380802	27.43	28.96	0.636	DUP	broken veins	VA05060560	1.53
2	1	0.2	0.4	40																		B380803	28.96	30.48	0.053			VA05060560	1.52
0.2	1	0.2	0.4	40																		B380804	30.48	32.00	0.040			VA05060560	1.52
0																						B380805	32.00	33.53	0.009			VA05060560	1.53
1	1	73.0											1.0									B380806	33.53	35.05	0.007		broken	VA05060560	1.52
3	1	0.2	0.6	60																		B380807	35.05	36.58	<0.005			VA05060560	1.53
1	1	4.0																				B380808	36.58	38.10	0.023		broken into pc's	VA05060560	1.52
1	1	4.0																				B380809	36.58	38.10	0.021	PD/CA		VA05060560	1.52
																						B380810	STANDARD 6F		2.820	6F		VA05060560	
3	1	1.0	1.4	40	55								0.1									B380811	38.10	39.62	0.034			VA05060560	1.52
1	1																					B380812	39.62	41.95	0.092		broken pc's	VA05060560	2.33
	1	1.0																				B380813	41.95	42.67	0.008		broken pc's	VA05060560	0.72
3	1	0.5	0.9	50																		B380814	42.67	44.20	0.009		dissem aspy & py	VA05060560	1.53
2	1	2.0	3.0	50																		B380815	44.20	45.72	0.254		dissem aspy & py	VA05060560	1.52
																						B380816	BLANK		<0.005			VA05060560	
	1																					B380817	45.72	47.24	0.014		broken vns, diss py	VA05060560	1.52
1	1	3.0	3.0	60																		B380818	47.24	48.23	0.036			VA05060560	0.99
	3	0.1		10																		B380819	48.23	48.77	<0.005		vnlets	VA05060560	0.54
1	1	1.0																				B380820	48.77	50.29	0.007		broken vns, diss py	VA05060560	1.52
	4	0.1		10																		B380821	50.29	51.83	0.053		vnlets	VA05060560	1.54
	4	0.1		10																		B380822	50.29	51.83	0.038	DUP		VA05060560	1.54
0																						B380823	51.83	53.36	<0.005			VA05060560	1.53
	1	1.0																									broken		
	1	1.0																				B380824	53.36	54.86	<0.005		broken pc's	VA05060560	1.50
	3	0.1	45.0																			B380825	54.86	55.46	0.167		vnlets	VA05060560	0.60
0																						B380826	55.46	56.39	0.259			VA05060560	0.93
	6	0.1								3.0												B380827	56.39	57.91	0.015		vnlets, no preferred orientation	VA05060560	1.52
3	6	0.1	0.3	20						0.1												B380828	57.91	59.44	<0.005			VA05060560	1.53
3	6	0.1	0.3	20						0.1												B380829	57.91	59.44	<0.005	PD/CA		VA05060560	1.53
																						B380830	STANDARD 2B		3.430	2B		VA05060560	
0																						B380831	59.44	60.96	0.024			VA05060560	1.52
2	1	0.5	0.7	40						0.1												B380832	60.96	62.48	0.116			VA05060560	1.52
6	1	0.1	0.1	30						0.1												B380833	62.48	64.01	0.008			VA05060560	1.53
2	1	0.2	0.4	40						0.1												B380834	64.01	65.00	<0.005			VA05060560	0.99

DRILL LOG LEGEND P1 | DATE: July 8-10, 2005 | PAGE 3 of 6

DRILL HOLE # : DG05-293C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		65.00	65.33	Graphitic MSED. Black color, greasy feel. Foliations are folded and fractured w/ offset dextrally. Vning is qtz/cb and contains 2% py. Foliation @ 40°.		1				
80		65.33	66.41	Silicified MSED. Light grey, lim on frac. Foliation @ 60° to CA.		1				
80		66.41	67.06	Clay gouge, black to dark grey. Greasy feel--graphitic. Clay is soft and moldable. Frags of parent rock found w/in--black MSEDs.		1				
80		67.06	70.10	Silicified MSED. Light to dark grey, core is broken. No lim present. Foliation @ 67.06m--55-60°; @ 68.58m--55-60°. Dissem py from 67.26-67.46m. End of HQ.		2				
80		70.10	83.82	Beginning of NQ core @ 70.10m. Reduction in core size required due to cave and clay. MSED--silicified. Light grey to dark grey color. Foliation is difficult to see. Foliation @ 70.10m: not visible; @ 71.63m: 60-65°; @ 73.15m: 55-60°; @ 74.68m: 60-65°; @ 76.20m: 65-70°; @ 77.72m: 60-65°; @ 79.25m: 40-45°; @ 80.77m: not visible; @ 82.30m: too broken to measure. At 76.30m: 15cm black core--graphitic.		1	1		1	
80		83.82	86.87	Clay gouge--grey. Qtz & MSED frags present. No contact angle.		1		4	1	
80		86.87	89.92	Light grey MSED and gouge. Contact w/ gouge (from previous interval) @ 5° from CA. Gouge continues at this angle until 88.42m. After 85.38m, core is broken and mixed w/ gouge. Unable to determine angles or position.		1		3	1	
80		89.92	92.96	Light grey MSED. Foliation is more pronounced. Core begins to darken to brown/violet color. Foliation @ 50-55°.						
80		92.96	102.21	Core is dark grey/brown/violet. Foliation @ 92.96m: core broken; @ 94.49m: core broken; @ 96.01m: 30-35°; @ 97.54m: 35-40°; @ 99.06m: 45-50°; @ 100.58m: 50-55°. Core shows boudins w/ increased strain. @ 96.01m: core shows more strain. Foliation is crenulated, growth of qtz eyes. @ 98.81m: 3cm clay gouge @ 55° to CA.						
80		102.21	102.28	3cm qtz vn w/ 20% aspy. Vn runs @ 30°--same as sulphide vnlets throughout core.						
25	102.28-103.63	102.28	103.63	Mafic intrusive--porphoritic plag phenocrysts, some calcite. Groundmass shows chl alt'n--diabase. Qtz/cb vnlets throughout.			2		1	
80	103.63-166.12	103.63	114.30	MSED--light to dark grey. Very few vns. Cb on frac faces and as vnlets. Boudins present, increased shear. Foliation @ 103.63m: 65-70°; @ 105.16m: 45-50°; @ 106.68m: 55-60°; @ 108.20m: 60-65°; @ 109.73m: 55-60°; @ 111.25m: 50-55°; @ 112.78m: 55-60°. At 105.02m: 7cm clay gouge @ 50°; @ 108.04m: 6cm clay gouge @ 50°, MSED frags; @ 108.14m: 6cm clay gouge @ 50° to CA--mica.		2	2	1	1	
80		114.30	123.44	Silicious MSED. Light grey to dark grey. Foliation difficult to see in light grey core. Foliation @ 114.30: 80-85°; @ 115.82m: 45-50°; @ 117.35m: 50-55°; @ 118.87m: 60-65°; @ 120.40m: 65-70°. Few qtz vns sheeted set @ 17.06m. 3-0.2cm vns crosscuts foliation.		1	2	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8-10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3									2.0												B380835	65.00	65.33	<0.005		irregular shape, no measurable angle.	VA05060560	0.33
																						B380836	BLANK		<0.005			VA05060560	
2	1	0.2	0.4	55		0.1	s															B380837	65.33	66.41	0.082			VA05062472	1.08
0																						B380838	66.41	67.06	0.024			VA05062472	0.65
1	1	0.2	0.2	5																		B380839	67.06	68.58	0.318			VA05062472	1.52
2	4	0.1	0.2	30																		B380840	68.58	70.10	0.046			VA05062472	1.52
0																						B380841	70.10	71.63	<0.005		very poor recovery	VA05062472	1.53
0																						B380842	70.10	71.63	0.005	DUP		VA05062472	1.53
1	1	2.0	2.0	65																		B380843	71.63	73.15	0.006			VA05062472	1.52
4	6	0.1	0.4	60						0.1								90.0				B380844	73.15	74.68	0.094			VA05062472	1.53
1	1	2.0	2.0	65																		B380845	74.68	76.20	0.007			VA05062472	1.52
1	1	2.0	2.0	70																		B380846	76.20	77.72	0.072			VA05062472	1.52
2	1	1.0	1.0	55									0.1									B380847	77.72	79.25	0.012			VA05062472	1.53
1	1	0.2	0.2	60																		B380848	79.25	80.77	<0.005			VA05062472	1.52
1	1	0.2	0.2	60																		B380849	79.25	80.77	<0.005	PD/CA		VA05062472	1.52
																						B380850	STANDARD 4D		0.434	4D		VA05062472	
2	1	3.0	3.2	60									0.1									B380851	80.77	82.30	<0.005			VA05062472	1.53
2.5	1	0.2	0.4																			B380852	82.30	83.82	<0.005		broken	VA05062472	1.52
																						B380853	83.82	85.34	<0.005		gouge	VA05062472	1.52
0																						B380854	85.34	86.87	<0.005		gouge	VA05062472	1.53
3	3	0.1	0.3	10																		B380855	86.87	88.39	0.005		vnlets	VA05062472	1.52
																						B380856	BLANK		<0.005			VA05062472	
	3																					B380857	88.39	89.92	<0.005		broken vnlets	VA05062472	1.53
	3	0.1		55																		B380858	89.92	91.44	0.007			VA05062472	1.52
																						B380859	91.44	92.96	<0.005			VA05062472	1.52
4	6	0.1	0.4	60						1.0												B380860	92.96	94.49	0.013			VA05062472	1.53
1	1	0.5	0.5	80						1.0												B380861	94.49	96.01	<0.005			VA05062472	1.52
1	1	0.5	0.5	80						1.0												B380862	94.49	96.01	<0.005	DUP		VA05062472	1.52
	3	0.1		15																		B380863	96.01	97.54	<0.005			VA05062472	1.53
0																						B380864	97.54	99.06	<0.005			VA05062472	1.52
1	1	3.0	3.0	30																		B380865	99.06	100.58	<0.005			VA05062472	1.52
1	1	1.0	1.0	70																		B380866	100.58	102.21	<0.005			VA05062472	1.63
1	6	3.0	3.0	30		1.0	chl	3	0				20.0									B380867	102.21	102.28	4.640			VA05062472	0.07
6	3	0.1	0.6	20																		B380868	102.28	103.63	0.141			VA05062472	1.35
6	3	0.1	0.6	20																		B380869	102.28	103.63	0.148	PD/CA		VA05062472	1.35
																						B380870	STANDARD 5E		1.150	5E		VA05062472	
	1									0.1			10.0									B380871	103.63	105.16	0.918		irregular stringer, no discernable angle	VA05062472	1.53
	1									1.0												B380872	105.16	106.68	<0.005		broken pc's	VA05062472	1.52
1	1	2.0	2.0	40		1.0	chl	3	0		0.1											B380873	106.68	108.20	<0.005			VA05062472	1.52
	3	0.1		30																		B380874	108.20	109.73	0.043		vnlets	VA05062472	1.53
	3	0.1		30																		B380875	109.73	111.25	<0.005		vnlets	VA05062472	1.52
																						B380876	BLANK		<0.005			VA05062472	
4	1	0.2	0.8	80		2.0	s	4	0		0.1											B380877	111.25	112.78	<0.005			VA05062472	1.53
3	1	2.0	5.0	40		1.0	s	3	0	1.0			1.0									B380878	112.78	114.30	<0.005			VA05062472	1.52
2	4	0.2	4.0	10																		B380879	114.30	115.82	<0.005			VA05062472	1.52
3	1	0.2	0.6	30																		B380880	115.82	117.35	<0.005		crosscut foliation	VA05062472	1.53

DRILL LOG LEGEND P1

DRILL HOLE # : DG05-293C

DATE: July 8-10, 2005 PAGE 5 of 6

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		123.44	126.49	MSED light grey to brown/violet. Foliation @ 123.44m: 60-65°; @ 124.97m: 55-60°. Boudins still present. Cb vns present.		2	2	1	2	
80		126.49	131.06	Silicified MSED. Light grey to brown. Foliation more distinct in darker coloured core. Qtz fills irregular voids btwn foliations. Foliation @ 126.49m: 55-60°; @ 128.02m: 50-55°; @ 129.54m: 55-60°.		1	1	1	1	
80		131.06	132.59	MSED--easily scratchable. Foliation @ 60-65° to CA. Vns btwn foliation.		2	2	1	1	
80		132.59	134.11	Silicious MSED. Foliation difficult to see. Less alt'n, vns at low angles to CA.			1		1	
80		134.11	138.68	MSED--easily scratchable. Foliation @ 134.11m: 45-50°; @ 135.64m: 30-35°; @ 137.16m: 40-45°. Cb vns crosscut foliation, boudins still present.		2	2	1	1	
80		138.68	144.78	MSED--easily scratchable. Foliation @ 138.68m: 45-50°; @ 140.21m: 50-55°; @ 141.73m: 60-65°; @ 143.26m: 55-60°. Boudins no longer present.						
80		144.78	149.35	Silicious MSED interbedded w/ softer, more alt'd MSEDs. Silicious bands are light grey in color, and foliation is difficult to see. The remaining MSEDs are dark grey w/ highly visible foliation. Vns in this type follow foliation. Low angle qtz/cb vnlets cut all core. foliation @ 144.78m: 55-60°; @ 146.30m: 55-60°; @ 147.83m: 55-60°.		2	2	1	1	
80		149.35	152.40	Silicious MSED. Light to dark grey color. Foliation is difficult to distinguish in light grey MSED. Foliation @ 149.35m: 55-60°; @ 150.88m: 55-60°. Vns follow foliations.		1	1		1	
80		152.40	155.45	Dark grey MSED, easily scratched. Vns are irregular but follow foliation. Foliation @ 152.40m: 50-55°; @ 153.92m: 50-55°.		2	2	1	1	
80		155.45	158.03	Silicious MSED. Light to dark grey color. Foliation is difficult to distinguish in light grey MSED. Foliation @ 155.45m: 60-65°; @ 156.97m: 55-60°. @ 157.17m: 9cm qtz vns w/ 10% massive py in grey qtz. Follows foliation @ 55°. @157.32m: 25cm of qtz vns, follow foliation, but no distinction can be made where vns start and end. Vns interlaced w/ MSEDs. Massive po present--5%. Follow foliation.		1	1		1	
80		158.03	166.12	MSED. Soft, easily scratchable. Dark grey green to grey. Very few vns present. Those present are 2-3cm and follow foliation. Foliation @158.50m: 55-60°; @160.02m: 55-60°; @161.54m: 60-65°; @ 163.07m: 55-60°; @ 164.59m: 55-60°. Carb increases.		1	2	1	2	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 8-10th, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.2	0.6	30						0.1												B380881	117.35	118.87	<0.005			VA05062472	1.52
3	1	0.2	0.6	30						0.1												B380882	117.35	118.87	<0.005	DUP		VA05062472	1.52
0																						B380883	118.87	120.40	<0.005		recovery v.poor	VA05062472	1.53
	3			50																		B380884	120.40	121.92	0.011		vnlets	VA05062472	1.52
1	1	1.0	1.0	55		0.2	s	4	0													B380885	121.92	123.44	<0.005		btwn foliation	VA05062472	1.52
3	1	1.0	1.4	40						0.1												B380886	123.44	124.97	<0.005		btwn foliation	VA05062472	1.53
3	4	0.2	0.6	30																		B380887	124.97	126.49	<0.005		crosscut foliation	VA05062472	1.52
4	1																					B380888	126.49	128.02	0.013		irregular fill btwn foliation	VA05062472	1.53
4	1																					B380889	126.49	128.02	0.011	PD/CA		VA05062472	1.53
																						B380890	STANDARD 7G		4.560	7G		VA05062472	
	3			10																		B380891	128.02	129.54	0.008		vnlets	VA05062472	1.52
4	1	2.0	6.0	60																		B380892	129.54	131.06	0.008		crosscuts	VA05062472	1.52
6	1	3.0	9.0	50		3.0	chl	3	0	0.1												B380893	131.06	132.59	0.009			VA05062472	1.53
2	1	3.0	4.0	50		2.0	chl	2	0													B380894	132.59	134.11	0.010			VA05062472	1.52
4	1	1.0	3.0	50							0.1											B380895	134.11	135.64	<0.005			VA05062472	1.53
																						B380896	BLANK		<0.005			VA05062472	
4	1	2.0	3.0	70	60																	B380897	135.64	137.16	<0.005			VA05062472	1.52
1	4	0.5	0.5	20																		B380898	137.16	138.68	<0.005		follows foliation	VA05062472	1.52
3	1	1.0	2.5	50																		B380899	138.68	140.21	<0.005			VA05062472	1.53
4	1	1.0	2.5	50							0.1											B380900	140.21	141.73	<0.005			VA05062472	1.52
2	1	1.0	1.5	60																		B380901	141.73	143.26	<0.005			VA05062472	1.53
2	1	1.0	1.5	60																		B380902	141.73	143.26	<0.005	DUP		VA05062472	1.53
	4			45																		B380903	143.26	144.78	0.011		vnlets crosscut foliation	VA05062472	1.52
	4			30																		B380904	144.78	146.30	<0.005		vnlets crosscut foliation	VA05062472	1.52
	4			30																		B380905	146.30	147.83	<0.005		vnlets crosscut foliation	VA05062472	1.53
1	1	1.0	1.0	40																		B380906	147.83	149.35	<0.005			VA05062472	1.52
1	3	0.5	0.5	40																									
2	1	0.5	0.7	65		4.0	q	5	0													B380907	149.35	150.88	0.006			VA05062472	1.53
3	1	10.0	12.0	60							1.0											B380908	150.88	152.40	<0.005			VA05062472	1.52
3	1	10.0	12.0	60							1.0											B380909	150.88	152.40	<0.005	PD/CA		VA05062472	1.52
																						B380910	STANDARD 3C		0.092	3C		VA05062472	
2	1	0.2	0.4	70																		B380911	152.40	153.92	<0.005			VA05062472	1.52
2	1	1.0	2.0	55	65					0.1												B380912	153.92	155.45	<0.005			VA05062472	1.53
2	1	1.5	2.0	70																		B380913	155.45	156.97	<0.005			VA05062472	1.52
5	1	25.0	40.0	55						10	5.0											B380914	156.97	158.03	0.112			VA05062472	1.06
1	1	1.0	1.0	70																		B380915	158.03	158.50	<0.005			VA05062472	0.47
																						B380916	BLANK		<0.005			VA05062472	
1	1	1.0	1.0	70							0.1											B380917	158.50	160.02	<0.005			VA05062472	1.52
1	1	0.5	0.5	70																		B380918	160.02	161.54	<0.005			VA05062472	1.52
2	1	6.0	7.0	60						0.1												B380919	161.54	163.07	<0.005			VA05062472	1.53
1	3	0.2	0.2	20																							crosscuts foliation		
5	1	6.0	8.0	60																		B380920	163.07	164.59	0.006			VA05062472	1.52
4	1	0.1	0.4	40																		B380921	164.59	166.12	<0.005			VA05062472	1.53
4	1	0.1	0.4	40																		B380922	164.59	166.12	<0.005	DUP		VA05062472	1.53
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-294C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 833m

BEARING: 000 **DIP:** -50°

DATE STARTED: 15-Jul-05 **DATE COMPLETED:** 18-Jul-05

COORD SYSTEM: NAD 27: **EASTING:** 459080 **NORTHING:** 7100730

COORD SYSTEM: NAD 83: **EASTING:** 458961 **NORTHING:** 7100915

NAD 27 (CORRECTED for historic grid): **EASTING:** 459050 **NORTHING:** 7100740

LOGGED BY: Terry Croteau

SECTION LINE (historic grid): 459050E

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 52 ft, 15.85m

Deviation:

Casing: 52 ft, 15.85m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
4.57	13.72	OVB; Variable lithologies, coarse gravel
13.72	44.88	OVB; Breccia with fault gouge, highly alt'd
44.88	95.31	MSED
95.31	98.63	QZZ
98.63	155.63	MSED
155.63	157.17	QZZ
157.17	191.82	MSED
191.82	198.60	QZZ
198.60	234.70	MSED
234.70	237.00	HFLS
237.00	240.60	QZZ
240.60	268.22	MSED

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B380923 to B381004

Requisition #: MASP448STRGOL.05Q — Date Shipped: 22-Jul-05

Lab Record #: VA05062473, VA05063074 (3) — Date Received: 27-Jul-05, 29-Jul-05

Sample Sequence: B381005 to B381110

Requisition #: MASP448STRGOL.05Q — Date Shipped: 17-Jul-05

Lab Record #: VA05064959 — Date Received: 9-Aug-05

Sample Sequence: B381111 to B381180

Requisition #: MASP448STRGOL.05Q — Date Shipped: 17-Jul-05

Lab Record #: VA05066289 — Date Received: 12-Aug-05

Duplicates:	B380942, B380962, B380982,B381002, B381022, B381042, B381062, B381082, B381102, B381122, B381142, B381162
Preparation Duplicate/ Check Assay:	B380929, B380949, B380969, B380989,B381009, B381029, B381049, B381069, B381089, B381109, B381129, B381149, B381169,
Standards:	B380930 (2B), B380950 (6F), B380970 (5E), B380990 (3C), B381010 (6F), B381030 (4D), B381050 (1A), B381070 (3C), B381090 (2B), B381110 (5E), B381130 (4D), B381150 (5E), B381170 (3C)
Blanks:	B380936, B380956, B380976, B380996, B381016, B381036, B3810456, B381076, B381096, B381116, B381136, B381156, B381176

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	DIP (+ 27 Corr)
60	002.5	-50.5	028.5	029.5
121.92	007.5	-52.3	033.5	034.5
182.88	009	-55.3	035	036
268.21	018.7	-57.9	044.7	045.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 16-28, 2005 PAGE 1 of 12		
DRILL HOLE # : DG05-294C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 4.57			Casing - No Recovery						
1	4.57 - 13.72	4.57	10.67	OVB: Core consists of GND, MSED, QZZ fragments. GND is solid, core with intervals of gravel to cobble size.	1					
1		10.67	13.72	Clay gouge; Clay mixed with pebble and gravel sized pieces with diverse lithology; Contact with breccia at 56° TCA; 3m sample, very poor recovery.						
1	13.72 - 44.88	13.72	15.24	Beginning of a 24.71m zone of breccia and gouge; Cb alt'n is dominant; Limonite is pervasive in the gouge; Recovery is poor. 40cm of breccia contact with MSED @ 30° TCA; Clast size ranges from 1mm to 1cm, with 80% from 2-.5cm; They appear to be unsorted and oriented to follow the 30° angle of the MSED contact; Py found in matrix					1	
1		15.24	16.76	Clay gouge; Hematite is pervasive; Original foliation preserved; At 15.26m, 55° TCA; Dark grey MSED frags present; Contact with breccia not present	3	2		4		
1		16.76	19.81	Breccia and clay gouge; Clasts are larger and sub-angular; Py fills fractures; No contact angle; Gouge at 18.09m; Pervasive limonite; Relict brecciated vein 3cm wide at 18.11m; At 19.51m returns to breccia.	3			3	1	
1		19.81	22.56	Breccia; Carb alt'n increases; Matrix now contains carbonate; Quartz veins are fractured and filled with carbonate; Clasts in the breccia are larger, up to 4cm with 80% 0.4 to 1.5cm; Clasts appear to follow 40° angle TCA; Slip direction appears normal.	3			3	3	
1		22.56	23.42	Breccia is black and shows intense clay alteration; No limonite present; At 23.09m, a 5cm qtz/cb vein at 85° TCA; Most veins in section fragmented and offset; Fractures filled with carbonate				3	1	
1		23.42	25.91	Core is much less brecciated with original foliation visible. At 24.68m, foliation at 30° TCA; Carbonate alteration is less intense; Pyrite visible in fractures in areas of clay alteration; At 25.31m, 44cm of clay alteration and gouge; Contact with breccia at 50° TCA; Minor limonite staining on fractured quartz veins.				3	1	
1		25.91	34.56	Breccia: Carbonate alteration dominant in matrix; Clasts range in size from 0.1cm to >5cm, with an average size of 1.5cm.; At 27.43m tension gashes filled with fragments and quartz and carbonate cement; Extensional - Normal fault?; Limonite is pervasive in gouge at 28.46m, 32.4m, 32.2m and 33.73m; At 37.91m Tension gashes and movement of clasts indicate extensional movement, likely high angle - gashes at 75° TCA.	1	1		2	2	
1		34.56	38.43	Breccia and gouge; Breccia is composed of smaller clasts 0.1 to 0.3cm with 80% 0.5cm; Gouge is dark grey, greasy feel, graphitic; Original lineation is visible at 36.68m; Foliation at 50° to 55° TCA; Gouge contains qtz and MSED frags; At 33.46m = 20cm clay gouge; At 35.46m = 57cm clay gouge.	1	1		2	2	
1		38.43	44.88	Fault Zone; Dark grey; Contact with breccia at 20° TCA; Qtz eyes and MSED porphyroclasts; At 38.25m = Most intense deformation, 80cm dark grey, graphitic with abundant qtz eyes. Porphyroclasts contain disseminated pyrite; Contact is breccia at 20° TCA; Contact angles between breccia/fault/gouge at 39.24m at 40° TCA; At 41.15m, at 45° TCA. At 42.67m, at 56° TCA; At 44.2m, at 50° TCA; Clay alteration tends to follow relic foliation angles at 60°.	1	1		2	2	
80	44.88 - 95.31	44.88	48.77	MSED and gouge/heavy clay alteration along foliations; Carbonate alteration present mostly on fracture faces; Contact with fault zone at 60° TCA.; Foliation at 44.88m, at 25-30° TCA; At 45.72m foliation at 35-40° TCA; At 47.24m foliation at 45-50° TCA.		1		4	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 2 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B380923	4.57	6.10	<0.005			VA05062473	1.53
																						B380924	6.10	7.62	<0.005			VA05062473	1.52
																						B380925	7.62	9.14	<0.005			VA05062473	1.52
																						B380926	9.14	10.67	<0.005			VA05062473	1.53
																						B380927	10.67	13.72	0.01		3 m sample	VA05062473	3.05
0										0.1												B380928	13.72	15.24	<0.005		Py found in mtx	VA05062473	1.52
0										0.1												B380929	13.72	15.24	<0.005	PD/CA		VA05062473	1.52
																						B380930	STANDARD 2B		3.02	2B		VA05062473	
0																						B380931	15.24	16.76	0.01			VA05062473	1.52
0																						B380932	16.76	18.29	<0.005			VA05062473	1.53
0																						B380933	18.29	19.81	0.01			VA05062473	1.52
1	4	0.2	0.2	85																		B380934	19.81	21.34	0.02			VA05062473	1.53
0																						B380935	21.34	22.56	<0.005			VA05062473	1.22
0																						B380936	BLANK		<0.005			VA05062473	
3	3	5.0	8.0	85																		B380937	22.56	23.42	<0.005			VA05062473	0.86
2	3	4.0	4.5	70																		B380938	23.42	24.55	<0.005			VA05062473	1.13
3	3	1.0	2.5	55	75					1.0												B380939	24.55	25.91	<0.005			VA05062473	1.36
3	6	0.1	0.3	60						1.0												B380940	25.91	27.43	<0.005			VA05062473	1.52
0																						B380941	27.43	28.96	<0.005			VA05062473	1.53
0																						B380942	27.43	28.96	<0.005	DUP		VA05062473	1.53
3	6	0.1	0.3	60						1.0												B380943	28.96	30.48	<0.005			VA05062473	1.52
0																						B380944	30.48	32.00	<0.005			VA05062473	1.52
0																						B380945	32.00	33.53	<0.005			VA05062473	1.53
4	6	0.1	0.4	60						1.0												B380946	33.53	34.56	<0.005			VA05062473	1.03
0																						B380947	34.56	35.05	<0.005			VA05062473	0.49
0																						B380948	35.05	36.58	<0.005			VA05062473	1.53
0																						B380949	35.05	36.58	<0.005	PD/CA		VA05062473	1.53
																						B380950	STANDARD 6F		2.54	6F		VA05062473	
1	1	1.0																				B380951	36.58	38.10	<0.005		Brcc'd. Diss py	VA05062473	1.52
0																						B380952	38.10	38.43	<0.005			VA05062473	0.33
																						B380953	38.43	39.62	<0.005			VA05062473	1.19
0																						B380954	39.62	41.15	<0.005			VA05062473	1.53
0																						B380955	41.15	42.67	<0.005			VA05062473	1.52
																						B380956	BLANK		<0.005			VA05062473	
0																						B380957	42.67	44.20	0.01			VA05062473	1.53
0																						B380958	44.20	44.88	0.03			VA05062473	0.68
0																						B380959	44.88	45.72	0.01			VA05062473	0.84
2	1	2.0	0.4	45																		B380960	45.72	47.24	<0.005			VA05062473	1.52
2	3	1.0	1.4	45																		B380961	47.24	48.77	<0.005			VA05062473	1.53
2	3	1.0	1.4	45																		B380962	47.24	48.77	<0.005	DUP		VA05062473	1.53

DRILL LOG LEGEND P1	DATE: July 16-28, 2005	PAGE 3 of 12	
DRILL HOLE # : DG05-294C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		48.77	53.34	MSED (phyllitic); Dark grey to reddish brown bands, soft and easy to scratch; Several sections contain more siliceous MSED between foliations, but showing no foliation themselves. These sections are a maximum of 0.8cm long. Foliations at 48.77m, at 47-50° TCA; At 50.29m, at 45-50° TCA; at 51.82m, at 35-40° TCA.		1	1	1	2	3
80		53.34	54.86	MSED; Intense clay alteration between foliations; Unaltered areas are more siliceous and show no visible foliations; At 53.34m 10cm of sticky, malleable clay, grey in color.		1		4	2	
80		54.86	57.35	MSED; Brown to grey-blue in color; Very strong effervescence between foliations with HCL; Foliations at 55-60°.				2	5	
80		57.35	57.91	MSED; Possibly carbonaceous; Core is black and very fine laminations present; Minor clay alteration; Foliation at 75° TCA.				2		
80		57.91	59.44	QZZ and Argillite (MSED); No foliation in QZZ or arg, Contacts at 30° and 75°; 75° more common; Cb veins abundant at 10-30°.				2	2	
80		59.44	62.48	MSED and Argillite; Core is dark grey to black; MSED shows intense alteration, much less in Argillite; Argillite is carbonaceous; At 60.96m, 25cm of siliceous MSED; Foliation where visible is 55° to 60° TCA.				4		
80		62.48	70.48	Siliceous MSED 90% and QZZ 10%; MSED is light brown to grey; QZZ contact angles follow foliations, but contain no visible foliation; Foliations at 62.48m = 75-80° TCA; 64.01 m = 80-85° TCA; 65.53m = 70-75° TCA; 67.06m = 80-85° TCA; 68.58m = 70-75° TCA; 70.10m = 70-75° TCA; MSED is phyllitic; At 62.48m = 9cm sandy gouge - No contact; At 63.92m = 8cm clay gouge = no contact; At 69.90m = 9cm sandy gouge at 75° TCA				2	1	
80		70.48	78.58	QZZ (MSED); QZZ with interbedded siliceous MSED; Foliation is visible in the MSED at 65-70° TCA; There is an increase in the qtz vein size and intensity; They appear in the MSED and follow foliation; Trace pyrrhotite present in veins; At 78.52m a 0.2 cm sulphide vein with 40% pyrrhotite.			2	1		
80		78.58	83.82	Siliceous MSED; Qtz veins still present; 2cm-7cm wide; Foliation at 78.58m = 60-65° TCA; At 79.25m = 55-60° TCA; At 80.77m = 55-60° TCA; At 82.3m = 55-60° TCA; Core is light grey, veins between foliations			1	1		
80		83.82	89.29	MSED; Moderate to intense clay alteration between foliations; Foliations at 83.82m at 65-70° TCA; At 85.39m at 65-70° TCA; At 86.62m at 55-60° TCA (crenulation cleavage); Becomes parallel TCA at 87.99-88.39m; At 88.39m is 70-72° TCA; At 85.72-86.62m = 0.2cm py vn running parallel TCA.		2	2	3		
80		89.29	95.31	MSED; Dark Grey to black, phyllitic; Foliation at 89.29m = 50-52° TCA; At 89.92m = 55-60° TCA; At 91.44m = 50-55° TCA; 92.96m = 50-52° TCA; 94.49m = 55-60° TCA; Qtz veins found between foliations; Low angle carbonate veins common (10-30° TCA)						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	1.5	1.5	55																		B380963	48.77	50.29	<0.005			VA05062473	1.52
3	1	0.2	0.6	50																		B380964	50.29	51.82	<0.005			VA05062473	1.53
2	3	0.5	1.0	35	10																	B380965	51.82	53.34	<0.005			VA05062473	1.52
1	3	0.5	0.5	50																		B380966	53.34	54.86	0.01			VA05062473	1.52
4	4	1.0	1.6	30																		B380967	54.86	56.39	<0.005			VA05062473	1.53
	4			30																		B380968	56.39	57.35	<0.005		Veinlets	VA05062473	0.96
	4			30																		B380969	56.39	57.35	<0.005	PD/CA		VA05062473	0.96
																						B380970	STANDARD 5E		1.43	5E		VA05062473	
0																						B380971	57.35	57.91	<0.005			VA05062473	0.56
1	1	2.5	2.5	50						1.0												B380972	57.91	59.44	<0.005		Min'n in clay alt'n surrounding the vein	VA05062473	1.53
2	4			60																		B380973	59.44	60.96	<0.005		Veinlets cross cut foliation	VA05062473	1.52
2	4																					B380974	60.96	62.48	<0.005			VA05062473	1.52
3	4	1.0	4.0	60																		B380975	62.48	64.01	<0.005			VA05062473	1.53
																						B380976	BLANK		<0.005			VA05062473	
	4			10	30																	B380977	64.01	65.53	<0.005		Veinlets	VA05062473	1.52
	4			20	30																	B380978	65.53	67.06	<0.005		Veinlets	VA05062473	1.53
2	4	0.1	0.2	30	20																	B380979	67.06	68.58	<0.005		Veinlets	VA05062473	1.52
3	4	0.1	0.3	20	25																	B380980	68.58	70.10	<0.005		Veinlets	VA05062473	1.52
	4																					B380981	70.10	70.48	0.04		Veinlets follow foliation	VA05062473	0.38
	4																					B380982	70.10	70.48	<0.005	DUP		VA05062473	0.38
0																						B380983	70.48	71.63	0.01			VA05062473	1.15
2	1	0.3	0.6	70						0.1												B380984	71.63	73.15	<0.005			VA05062473	1.52
	4																					B380985	73.15	74.68	<0.005		Veinlets follow fractures	VA05062473	1.53
1	3	0.1	0.1	40																		B380986	74.68	76.20	<0.005			VA05062473	1.52
6	1	7.0	13.5	80																		B380987	76.20	77.72	0.01			VA05062473	1.52
1	6	0.2	0.2	65							40.0											B380988	77.72	78.58	<0.005			VA05062473	0.86
1	6	0.2	0.2	65							40.0											B380989	77.72	78.58	0.01	PD/CA		VA05062473	0.86
																						B380990	STANDARD 3C		0.09	3C		VA05062473	
2	1	0.2	0.4	80																		B380991	78.58	79.25	<0.005			VA05063074	0.67
4	1	7.0	9.5	70																		B380992	79.25	80.77	0.01			VA05063074	1.52
3	1	5.0	8.0	75							3.0	0.1						40.0				B380993	80.77	82.30	0.01			VA05063074	1.53
2	1	6.0	6.5	70									0.1					90.0				B380994	82.30	83.82	0.25			VA05063074	1.52
0																						B380995	83.82	85.39	0.17			VA05062473	1.57
																						B380996	BLANK		<0.005			VA05062473	
0																						B380997	85.39	85.72	0.01			VA05062473	0.33
1	6	0.2	0.2	0	5					30.0												B380998	85.72	86.62	0.64			VA05062473	0.90
	1	0.2																				B380999	86.62	88.39	<0.005		Broken pieces	VA05062473	1.77
	1	1.0									0.1											B381000	88.39	89.29	<0.005		Quartz eyes and broken pieces	VA05062473	0.90
1	1	1.0	1.0	50									0.1									B381001	89.29	89.92	<0.005			VA05062473	0.63
1	1	1.0	1.0	50									0.1									B381002	89.29	89.92	<0.005	DUP		VA05062473	0.63
3	1	0.5	0.9	70																		B381003	89.92	91.44	<0.005			VA05062473	1.52
3	1	0.2	0.6	55																		B381004	91.44	92.96	<0.005		Irregular shape btw fol	VA05062473	1.52
1	1	0.2	0.2	25																		B381005	92.96	94.49	<0.005			VA05064959	1.53
0																						B381006	94.49	95.31	<0.005			VA05064959	0.82

DRILL HOLE # : DG05-294C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd

Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered

Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70	95.31 - 98.63	95.31	98.63	QZZ; Light grey coloured, highly fractured; Hosts several large quartz veins (3-10cm); Veins are also highly fractured or broken; Trace to 1% oxidized pyrite found on fracture faces; Fracture angles varied 30-50°, crosscut by 150-165°.						
80	98.63 - 155.63	98.63	99.54	MSED: Intense clay and sericite alteration of MSED; No visible foliation angles; Unaltered MSED fragmented into gravel sized pieces, phyllitic; No visible foliation.		2		3		
80		99.54	102.11	MSED: Light to dark grey, phyllitic; Foliation at 99.54m = 50-52°; At 100.58m = 40-42° TCA; At 100.58m, 12cm argillite before change in foliation angle		1		1		
80		102.11	113.30	MSED: Core is soft easily scratchable; phyllitic; dark grey color. Foliations: at 102.11m = 55-60° TCA; At 103.63m = 45-50° TCA; At 105.16m = 40-45° TCA; At 106.68m = 45-50° TCA; At 108.2m = 45-50° TCA; At 109.73m = 45-50° TCA; At 111.25m = 45-50° TCA; 112.78m = 45-50° TCA: Quartz veins between foliations. The number of carb veinlets are reduced.		2	2	2	1	
80		113.30	115.82	Siliceous MSED: Light grey color; Increase in qtz and carb veins over interval; Qtz veins follow foliations where visible; Carb veinlets crosscut foliation at 113.3m = 40-45°; At 114.3m = 45-50° TCA						
80		115.82	118.87	MSED Light to dark grey; Phyllitic Qtz/Cb veins follow foliations; Cb veins crosscut foliations at 115.82m = 50-52° TCA; At 117.35m = 35-40° TCA; Clay alteration is increased after 117.35m		3	2	2	1	
80		118.87	121.92	MSED light grey-green; Chl alteration dominant, but sericite and clay still present; Cb veins continue to crosscut foliation; Foliation at 118.87m = 70-75°; At 120.40m = 65-70° TCA; 121.92m = 40-45° TCA		2	3	2	1	
80		121.92	122.47	Silicified MSED with crosscutting qtz veinlets and sulphide veins; Cb veinlets present.					2	
80		122.47	128.02	MSED: Intense clay alteration, light to dark grey color; Quartz between foliation; Foliation at 121.92m = 35-40° TCA; At 123.44m = 40-45° TCA; At 124.97m = 45-50° TCA; At 126.49m = 50-55° TCA; At 125.34m = 40cm clay gouge contains remnant MSED frags; At 127.22m = 60cm clay gouge with remnant MSED frags.		2	1	3	1	
80		128.02	129.94	MSED: Clay alteration greatly reduced; Chlorite alteration increased on fractures; Carbonate veins at low angle, cross cut foliation; Foliation at 128.02m = 35-40° TCA; At 129.54m = 40-45° TCA.		1	2	2	1	
80		129.94	132.28	Argillite (MSED): Dark grey, no foliation; Cb veinlets abundant.						
80		132.28	134.11	MSED: Dark grey-brown phyllitic; Fewer Cb veins/veinlets; Foliation at 132.28m = 85-90° TCA; At 132.59m = 45-50° TCA.		1	2		1	
80		134.11	135.64	Siliceous MSED: Dark grey-black; Qtz veins follow foliation; Cb altered and veining greatly reduced; Foliation at 60° TCA.						
80		135.64	141.23	MSED: Dark grey to black; Cb veinlets almost completely absent: Qtz veins between foliations; Po appears in veins; Foliations...At 135.64m = 55-60° TCA; At 137.16m = 50-55° TCA; At 138.68m = 55-60° TCA; At 140.61m = 40-42° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 6 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. Slate 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B381007	95.31	96.01	0.02			VA05064959	0.70
6	1	3.0	13.5	30									0.1					95.0				B381008	96.01	97.54	0.01			VA05064959	1.53
6	1	3.0	13.5	30									0.1					95.0				B381009	96.01	97.54	0.04	PD/CA		VA05064959	1.53
																						B381010	STANDARD 6F		2.88	6F		VA05064959	
0																						B381011	97.54	98.63	0.01			VA05064959	1.09
0																						B381012	98.63	99.06	0.07			VA05064959	0.43
0																						B381013	99.06	99.54	<0.005			VA05064959	0.48
0																						B381014	99.54	100.58	<0.005			VA05064959	1.04
2	1	0.2	0.4	55																		B381015	100.58	102.11	<0.005			VA05064959	1.53
																						B381016	BLANK		<0.005			VA05064959	
1	1	2.0	2.0	50									2.0									B381017	102.11	103.63	0.20			VA05064959	1.52
0																						B381018	103.63	105.16	<0.005			VA05064959	1.53
1	1	1.0	1.0	40									0.1									B381019	105.16	106.68	<0.005			VA05064959	1.52
3	1	3.0	4.0	60									0.1									B381020	106.68	108.20	<0.005			VA05064959	1.52
2	3	1.0	1.5	35																		B381021	108.20	109.73	<0.005			VA05064959	1.53
2	3	1.0	1.5	35																		B381022	108.20	109.73	<0.005	DUP		VA05064959	1.53
3	1	2.0	5.0	50																		B381023	109.73	111.25	0.02			VA05064959	1.52
2	3	2.0	3.0	50						3.0												B381024	111.25	112.78	0.04			VA05064959	1.53
0																						B381025	112.78	113.30	<0.005			VA05064959	0.52
2	4	0.2	0.4	50																		B381026	113.30	114.30	0.02			VA05064959	1.00
1	1	2.0	2.0	45																		B381027	114.30	115.82	0.01			VA05064959	1.52
	4			175	180																						Veinlets cross cut foliation		
																						B381028	115.82	117.35	0.01			VA05064959	1.53
																						B381029	115.82	117.35	0.01	PD/CA		VA05064959	1.53
																						B381030	STANDARD 4D		0.45	4D		VA05064959	
																						B381031	117.35	118.87	<0.005			VA05064959	1.52
	3			170	180																	B381032	118.87	120.40	0.01		Veinlets low angle crosscut	VA05064959	1.53
	3			170	180																	B381033	120.40	121.92	0.02		Veinlets low angle crosscut	VA05064959	1.52
4	1	5.0	9.0	45																		B381034	121.92	122.47	0.01			VA05064959	0.55
3	6	1.0	1.7	135									40.0						90.0										
0																						B381035	122.47	123.44	0.02			VA05064959	0.97
																						B381036	BLANK		<0.005			VA05064959	
0																						B381037	123.44	124.97	<0.005			VA05064959	1.53
1	1	2.5	2.5	45																		B381038	124.97	126.49	<0.005			VA05064959	1.52
0																						B381039	126.49	128.02	0.06			VA05064959	1.53
3	4	0.2	0.6	10	30																	B381040	128.02	129.54	<0.005			VA05064959	1.52
1	3	1.0	1.0	75																		B381041	129.54	129.94	<0.005			VA05064959	0.40
1	3	1.0	1.0	75																		B381042	129.54	129.94	<0.005	DUP		VA05064959	0.40
0																						B381043	129.94	130.30	<0.005			VA05064959	0.36
0																						B381044	130.30	131.06	<0.005			VA05064959	0.76
0																						B381045	131.06	132.28	<0.005			VA05064959	1.22
0																						B381046	132.28	132.59	<0.005			VA05064959	0.31
2	4	1.0	1.5	40																		B381047	132.59	134.11	<0.005			VA05064959	1.52
2	1	1.0	1.5	55																		B381048	134.11	135.64	<0.005			VA05064959	1.53
2	1	1.0	1.5	55																		B381049	134.11	135.64	<0.005	PD/CA		VA05064959	1.53
																						B381050	STANDARD 1A		0.80	1A		VA05064959	
0																						B381051	135.64	137.16	<0.005			VA05064959	1.52

DRILL LOG LEGEND - P1	DATE: July 16-28, 2005	PAGE 7 of 12	
DRILL HOLE # : DG05-294C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		141.23	143.92	MSED: Core is light to dark grey; Intense clay alteration and sericite alteration; Foliation difficult to see due to alteration; Foliation: At 141.23m = too altered; At 141.73m = 55-60° TCA; At 143.26m = 55-60° TCA.		2	2	4	1	
80		143.92	144.58	MSED: Dark grey siliceous MSED; Qtz veins between foliations; Foliation at 50-52° TCA.		1	1			
80		144.58	155.63	MSED: Grey to dark grey; Qtz veins between foliations; Foliations...At 144.58m = 50-55° TCA; At 146.3m = 55-60° TCA; At 147.83m = 65-70° TCA; At 149.35m = 60-65° TCA; At 150.88m = 55-60° TCA; At 152.4m = 50-55° TCA; At 153.92m = 45-50°; Phyllitic...At 147.61m = 23cm QZZ; Diss py on fracture faces.		2	2	2	1	
70	155.63 - 157.17	155.63	157.17	QZZ: Light grey in color; Low angle Cb veins are common; Core is highly fractured and broken.					2	
80	157.17 - 191.82	157.17	160.74	MSED: Dark grey phyllitic QZZ veins follow foliations; Cb veinlets present are fewer in number than previous; Foliation at 157.17 is 60-62° TCA; At 158.5m = 65-70° TCA; At 160.02 m = 65-70° TCA		2	2	2	1	
80		160.74	161.87	Siliceous MSED: Cb veinlets more common; Foliation at 55-62° TCA		2			2	
80		161.87	171.71	MSED: Dark grey to black; Carbonaceous Phyllitic; Qtz veins between foliations; Cb fills fractures in veins; Increase in Cb veins and veinlets which crosscut foliations; Foliations: @161.87m = 65-70° TCA; At 163.07m = 55-60° TCA; At 164.59m = 50-55° TCA; At 166.12m = 45-50° TCA; At 167.64m = 60-65° TCA; At 169.16m = 55-60° TCA; At 170.69m = 30-35° TCA: At 171.11m = 10cm fault gouge at 40° TCA, cut through 5cm qtz veins containing scorodite (1%); Foliation after fault 55-60° TCA		3	2	1	2	
80		171.71	171.87	MSED: 16cm qtz vein at 60° TCA; Grey quartz follows adjacent foliations; 1% po present; Trace aspy						
80		171.87	173.12	Siliceous MSED: Foliations difficult to see; Where visible, at 70° TCA, containing boudins					1	
80		173.12	174.76	Dark grey MSED: Contains boudins; Foliation at 47-50° TCA.		2	2	1	1	
80		174.76	177.18	Silicified MSED: Qtz veins larger (2-7cm) in this section; Foliation 55° TCA; Qtz veins have large selvages					1	
80		177.18	191.82	MSED: Light to dark grey color; Qtz veins follow foliation; Sulphide veinlets cross cut; Most sulphide veins/veinlets have been replaced by a soft, brown groundmass likely bt; Aspy tends to be altered to scorodite; Foliations: At 177.18m = 70° TCA; At 178.31m = 60-65° TCA; At 179.83m = 55-60° TCA; At 181.36m = 45-50° TCA; At 182.88m = 55-60° TCA; At 184.4m = 50-55° TCA; Carbonaceous and phyllitic		3	2	2	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 8 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
0																						B381052	137.16	138.68	<0.005			VA05064959	1.52
4	1	3.0	9.0	65							1.0											B381053	138.68	140.21	<0.005			VA05064959	1.53
1	1	3.0	3.0																			B381054	140.21	141.23	<0.005		Broken Pieces	VA05064959	1.02
0																						B381055	141.23	141.73	0.01			VA05064959	0.50
																						B381056	BLANK		<0.005			VA05064959	
2	1	0.2	0.4	60																		B381057	141.73	143.26	<0.005			VA05064959	1.53
2	1	0.2	0.4	60																		B381058	143.26	143.92	<0.005			VA05064959	0.66
6	1	0.2	1.2	50																		B381059	143.92	144.58	<0.005			VA05064959	0.66
3	1	0.2	0.6	50							0.1											B381060	144.58	146.30	<0.005			VA05064959	1.72
1	1	0.2	0.2	50																		B381061	146.30	147.83	<0.005			VA05064959	1.53
1	1	0.2	0.2	50																		B381062	146.30	147.83	<0.005	DUP		VA05064959	1.53
5	1	0.2	1.0	50																		B381063	147.83	149.35	<0.005			VA05064959	1.52
5	1	0.2	1.0	50																		B381064	149.35	150.88	<0.005			VA05064959	1.53
3	3	5.0	9.0	50																		B381065	150.88	152.40	<0.005			VA05064959	1.52
2	1	0.5	0.7	65																		B381066	152.40	153.92	<0.005			VA05064959	1.52
3	1	3.0	7.0	60							0.1											B381067	153.92	155.63	<0.005			VA05064959	1.71
5	6	0.1	0.5	30	60					30.0			20.0									B381068	155.63	157.17	0.03		Sulphide Veinlets	VA05064959	1.54
5	6	0.1	0.5	30	60					30.0			20.0									B381069	155.63	157.17	0.02	PD/CA		VA05064959	1.54
																						B381070	STANDARD 3C		0.09	3C		VA05064959	
2	1	3.0	5.0	60		3.0	chl	3	0	0.1												B381071	157.17	158.50	<0.005			VA05064959	1.33
5	1	3.0	8.0	60						0.1												B381072	158.50	160.02	<0.005			VA05064959	1.52
0																						B381073	160.02	160.74	<0.005			VA05064959	0.72
	4	0.1	30.0																			B381074	160.74	161.87	<0.005		Veinlets	VA05064959	1.13
3	1	0.2	0.6	75																		B381075	161.87	163.07	<0.005			VA05064959	1.20
																						B381076	BLANK		<0.005			VA05064959	
2	1	1.0	1.5	60																		B381077	163.07	164.59	<0.005			VA05064959	1.52
2	4	0.5	0.7	30																									
4	1	1.0	3.5	50																		B381078	164.59	166.12	<0.005			VA05064959	1.53
3	1	0.2	0.6	60																		B381079	166.12	167.64	<0.005			VA05064959	1.52
3	1	0.5	1.5	50																		B381080	167.64	169.16	0.02			VA05064959	1.52
0																						B381081	169.16	170.69	0.02			VA05064959	1.53
0																						B381082	169.16	170.69	0.01	DUP		VA05064959	1.53
1	1	5.0	5.0	40									0.1						90.0			B381083	170.69	171.71	<0.005			VA05064959	1.02
1	1	16.0	16.0	60							1.0		0.1					20.0				B381084	171.71	171.87	<0.005			VA05064959	0.16
																						B381085	171.87	173.12	<0.005			VA05064959	1.25
1		1.5	1.5	60									0.1						90.0			B381086	173.12	174.76	<0.005			VA05064959	1.64
6	1	6.0	12.0	50									5.0						90.0			B381087	174.76	175.26	0.09			VA05064959	0.50
4	1	2.0	5.5	55							3.0											B381088	175.26	176.78	0.01			VA05064959	1.52
4	1	2.0	5.5	55							3.0											B381089	175.26	176.78	0.01	PD/CA		VA05064959	1.52
																						B381090	STANDARD 2B		2.96	2B		VA05064959	
1	6	0.4	0.4	30																		B381091	176.78	177.18	<0.005		Sulphide replaced by fine grey-brown groundmass (biot?)	VA05064959	0.40
2	4	0.2	0.4	35																		B381092	177.18	178.31	<0.005		Crosscuts foliation	VA05064959	1.13
2	1	0.2	0.4	55																		B381093	178.31	179.83	<0.005			VA05064959	1.52
2	1	1.5	3.0	55																		B381094	179.83	181.36	0.01			VA05064959	1.53
2	6	0.2	0.4	135																									
4	1	0.2	0.8	55																		B381095	181.36	182.88	0.02			VA05064959	1.52

DRILL LOG LEGEND P1	DATE: July 16-28, 2005	PAGE 9 of 12	
DRILL HOLE # : DG05-294C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70	191.82 - 198.60	191.82	198.60	QZZ: Light grey to brown; Foliation rarely visible; Very few veins (qtz and carb); Few Sulphide veinlets; Aspy altered to scorodite; Disseminated aspy found throughout -ox; Foliation at 55-60° where visible.					1	
80	198.60 - 234.70	198.60	202.34	MSED: Grey to dark grey; Phyllitic, Carbonaceous; Qtz Follows foliations, often irregular vein patterns; Foliations: At 198.6m = 60-65° TCA; At 199.64m = 65-70° TCA; At 201.17m = 45-60° TCA.		3	2	2	1	
80		202.34	205.54	Siliceous MSED: Light grey color; Increase in low angle cb veins; Foliations: At 202.34m = 52-55° TCA; At 204.22m = 65-70° TCA.					1	
80		205.54	209.79	MSED: Dark grey to black; Reduction in Carbonate veining; Qtz veins between foliation; Foliation: At 205.54m = 60-62° TCA; At 207.26m = 40-45° TCA crenulated; At 208.79m = 50-55° TCA boudins present; At 206.02m = 9cm grey quartz vein at 70° TCA; 1% py and 1% aspy.		2	1	2	1	
80		209.79	213.36	Siliceous MSED and QZZ; MSED grey, QZZ light grey; The QZZ has more veins, larger size and contains po (tr-1%) and disseminated po. Foliation: At 209.79m = 60-65° TCA; At 210.31m = Not visible; At 211.14m = 60-65° TCA; At 211.84m = 60-65° TCA; At 212.16m = Carb vein at 35° TCA; Contains 3% po; Carb veinlets also contain po.					1	
80		213.36	217.59	MSED: Grey to black; Very few veins present; Foliation: At 213.36m = 50-55° TCA; At 214.88m = 55-60° TCA; At 216.41m = 65-70° TCA; Boudins present after 215.52m.						
80		217.59	219.77	Siliceous MSED; Light grey color very little foliation visible; Foliation at 45-50°. At 217.59m a 40cm QZZ at 60° TCA.						
80		219.77	231.65	MSED: Dark grey to black; Phyllitic where dark grey, carbonaceous where black; Qtz veins crosscut foliation until 230.12m, where they run parallel. Foliation: At 220.98m = 60-65° TCA; At 222.5m = 55-60° TCA; At 224.03m = 55-60° TCA; At 225.55m - 50-55° TCA; At 227.08m = 45-50° TCA; At 228.60m = 55-60° TCA; At 230.12m = 60-62° TCA; At 220.11m = 2cm py vein at low angle 10-30° following contact with QZZ: The QZZ also has disseminated aspy, cpy; The contact between the two is a fault plane with 11-15cm of slip. Fault plane crosscut foliation; Slip was near vertical; Fault Zone is 40cm long at 25-30° TCA.		3	2	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B381096	BLANK		<0.005			VA05064959	
1	3	0.5	0.5	135						5.0												B381097	182.88	184.40	0.07		Crosscuts	VA05064959	1.52
2	1	0.5	1.0	60																		B381098	184.40	185.93	<0.005			VA05064959	1.53
5	1	2.0	4.0	50																		B381099	185.93	187.45	0.02			VA05064959	1.52
3	1	1.0	3.0	50																		B381100	187.45	188.98	<0.005			VA05064959	1.53
2	1	0.5	0.7	60																		B381101	188.98	190.50	<0.005			VA05064959	1.52
2	1	0.5	0.7	60																		B381102	188.98	190.50	<0.005	DUP		VA05064959	1.52
0																						B381103	190.50	191.82	<0.005			VA05064959	1.32
3	1	2.0	5.0	50						0.1								90.0				B381104	191.82	193.55	<0.005			VA05064959	1.73
	4	0.1		30																		B381105	193.55	195.07	<0.005		Veinlets	VA05064959	1.52
2	6	0.1	0.2	40						5.0								90.0				B381106	195.07	196.60	0.01			VA05064959	1.53
	4			60																		B381107	196.60	198.12	<0.005		Veinlets follow foliation	VA05064959	1.52
	4			60																		B381108	198.12	198.60	<0.005		Veinlets in between foliation	VA05064959	0.48
	4			60																		B381109	198.12	198.60	<0.005	PD/CA		VA05064959	0.48
																						B381110	STANDARD 5E		1.43	5E		VA05064959	
	4			60																		B381111	198.60	199.64	0.01		Veinlets	VA05066289	1.04
2	1	0.5	1.0	70																		B381112	199.64	201.17	<0.005			VA05066289	1.53
1	1	0.5	0.5	60																		B381113	201.17	202.34	0.01			VA05066289	1.17
	4			30																									
	4	0.1		40																		B381114	202.34	202.69	<0.005		Veinlets crosscut	VA05066289	0.35
5	1	4.0	7.0	60		0.1	q-k	3	0													B381115	202.69	204.22	<0.005			VA05066289	1.53
																						B381116	BLANK		<0.005			VA05066289	
2	6	0.1	0.2																			B381117	204.22	205.54	0.58		Sulphides replaced by brown fine grained mineral (biot?)	VA05066289	1.32
0																						B381118	205.54	206.02	<0.005			VA05066289	0.48
2	1	9.0	20.0	70						1.0			1.0									B381119	206.02	206.28	<0.005			VA05066289	0.26
	4			30																		B381120	206.28	207.26	<0.005		Veinlets, crosscut	VA05066289	0.98
0																						B381121	207.26	208.79	0.05			VA05066289	1.53
	4			30																		B381122	207.26	208.79	0.02	DUP	Veinlets Crosscut	VA05066289	1.53
	4			30																		B381123	208.79	209.79	<0.005			VA05066289	1.00
	4			30																		B381124	209.79	210.31	0.35			VA05066289	0.52
8	1	5.5	18.0	55						0.1			0.1									B381125	210.31	211.14	0.14			VA05066289	0.83
1	1	1.0	1.0	60																		B381126	211.14	211.84	0.01			VA05066289	0.70
1	4	0.2	0.2	145							3.0											B381127	211.84	213.36	0.18		Carb veinlets also contain po	VA05066289	1.52
1	1	1.0	1.0	60							1.0																		
	4	0.1		30	10																	B381128	213.36	214.88	<0.005		Veinlets crosscut	VA05066289	1.52
	4	0.1		30	10																	B381129	213.36	214.88	<0.005	PD/CA		VA05066289	1.52
																						B381130	STANDARD 4D		0.45	4D		VA05066289	
	4			60																		B381131	214.88	216.41	<0.005			VA05066289	1.53
	4			60																		B381132	216.41	217.59	<0.005			VA05066289	1.18
1	1	0.5	0.5	60																		B381133	217.59	219.19	0.01			VA05066289	1.60
2	1	3.0	6.0	60									0.1									B381134	219.19	219.77	0.05			VA05066289	0.58
0																						B381135	219.77	220.04	0.06			VA05066289	0.27
																						B381136	BLANK		<0.005			VA05066289	
2	6	2.0	2.2	10	20					60.0												B381137	220.04	220.62	0.18			VA05066289	0.58

DRILL HOLE # : DG05-294C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		231.65	234.70	Siliceous MSED; Light grey; Carbonate alteration increased, as has veining; Foliation: At 231.65m = 60-62° TCA; At 233.17m = 60-62° TCA; 233.24m = 46cm fault zone at 25° TCA, py present along slip and in folded qtz veins; Veins suffered intense cb alteration; Slip plane crosscuts foliation; Similar to FZ above.		1		1	1	
81	234.70 - 237.00	234.70	237.00	HFLS MSED - Green-violet color; Qtz veins irregular, between residual foliations; Disseminated pyrite found throughout; Cb veining increased, common foliation at 55-60° TCA.		3	2		2	
70	237.00 - 240.60	237.00	240.60	QZZ: Light grey to grey-green; At 237.24m = 10cm mafic intrusive = Diabase Dyke at 60° TCA; Increase in qtz veining frequency and size.					1	
80	240.60 - 268.22	240.60	249.94	MSED: Dark grey (phyllitic) to black (carbonaceous); Reduction in number of Carbonate veinlets and alteration as well as qtz veins. Foliation: At 240.60m = 60-62° TCA; At 242.32m = 60-62° TCA; At 243.84m = 60-65° TCA; At 245.36m = 50-55° TCA; At 246.89m = 60-62° TCA; At 248.41m = 60-62° TCA; At 246.79m = 56cm of QZZ at 60° TCA.		3	1	1	1	
80		249.94	257.56	Siliceous MSED: Light grey to grey; Siliceous; Increase in number and size of quartz veins; Foliation is visible in several locations; Foliation: At 249.94m = 45-50° TCA; At 251.46m = 60-62° TCA; At 252.98m = 60-62° TCA; At 254.51m = 40-45° TCA; At 256.03m = 50-52° TCA; At 251.24m = Mineralized slip plane at 155° TCA; Crosscuts foliation, 1cm pyrite present, also disseminated pyrite; Slip direction consistent with other slip planes (near vertical).		1			2	
80		257.56	268.22	Siliceous MSED: Dark grey, foliation more visible; Less silicification than previous interval; Foliation: At 257.56m = 60-62° TCA; At 259.08m = 40-45° TCA; At 260.6m = 50-55° TCA; At 262.13m = 55-60° TCA; At 263.65m = 55-60° TCA; At 265.18m = 42-45° TCA; At 266.7m = 58-60° TCA. At 264.05m = 49cm carbonaceous, black phyllitic MSED, contact at 80° TCA; At 265.4m = 7cm qtz vn at 85° TCA (up hole), 30° TCA down hole.		1	1	1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 16-28, 2005

LOGGED BY: T. Croteau

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	3	2.0	2.0	30						30.0												B381138	220.62	221.08	0.04		Vein is pink	VA05066289	0.46
3	6	2.0	2.2	10	20					10.0			10.0									B381139	221.08	222.50	0.14			VA05066289	1.42
1	1	1.0	1.0	60																		B381140	222.50	224.03	0.02			VA05066289	1.53
1	4	0.2	0.2	45																		B381141	224.03	225.55	<0.005			VA05066289	1.52
1	4	0.2	0.2	45																		B381142	224.30	225.55	<0.005	DUP		VA05066289	1.25
1	2	0.2	0.4	60																		B381143	225.55	227.08	<0.005			VA05066289	1.53
2	3	3.0	6.0	60							3.0											B381144	227.08	228.60	0.01			VA05066289	1.52
	4			10																		B381145	228.60	230.12	<0.005		Veinlets, crosscut foliation	VA05066289	1.52
	4			10																		B381146	230.12	231.65	<0.005		Veinlets, crosscut foliation	VA05066289	1.53
1	1	3.0	3.0	50																		B381147	231.65	233.17	<0.005			VA05066289	1.52
1	3	3.0	3.0	56																		B381148	233.17	234.70	<0.005			VA05066289	1.53
1	3	3.0	3.0	56																		B381149	233.17	234.70	0.01	PD/CA		VA05066289	1.53
																						B381150	STANDARD 5E		1.43	5E		VA05066289	
1	1	3.0	3.0	50							1.0		1.0						90.0			B381151	234.70	236.22	<0.005			VA05066289	1.52
2	1	1.0	1.2	70									0.1						50.0			B381152	236.22	237.00	<0.005			VA05066289	0.78
7	1	4.0	9.0	55							0.1											B381153	237.00	237.74	<0.005			VA05066289	0.74
5	1	4.0	12.0	55							0.1		1.0						90.0			B381154	237.74	239.27	<0.005			VA05066289	1.53
3	1	1.0	1.4	65							0.1											B381155	239.27	240.60	<0.005			VA05066289	1.33
																						B381156	BLANK		<0.005			VA05066289	
	4			30																		B381157	240.60	241.13	<0.005		Cb veinlets	VA05066289	0.53
	4			30																		B381158	241.13	242.32	<0.005		Veinlets	VA05066289	1.19
	4			30																		B381159	242.32	243.84	<0.005		Veinlets	VA05066289	1.52
	4			30	10																	B381160	243.84	245.36	<0.005		Veinlets	VA05066289	1.52
2	1	0.2	0.4	50							0.1											B381161	245.36	246.89	<0.005			VA05066289	1.53
2	1	0.2	0.4	50							0.1											B381162	245.36	246.89	<0.005	DUP		VA05066289	1.53
1	1	0.5	0.5	55																		B381163	246.89	248.41	0.01			VA05066289	1.52
3	4	0.2	0.6	70						0.1												B381164	248.41	249.94	0.02			VA05066289	1.53
3	1	2.0	4.0	60						3.0												B381165	249.94	251.24	0.01			VA05066289	1.30
1	6	0.5	0.5	30						90.0												B381166	251.24	251.46	0.02			VA05066289	0.22
3	1	1.0	1.7	70																		B381167	251.46	252.98	<0.005			VA05066289	1.52
2	4	0.5	1.0	25																		B381168	252.98	254.51	<0.005			VA05066289	1.53
2	4	0.5	1.0	25																		B381169	252.98	254.51	0.01	PD/CA		VA05066289	1.53
																						B381170	STANDARD 3C		0.09	3C		VA05066289	
1	1	1.0	1.0	55																		B381171	254.51	256.03	<0.005			VA05066289	1.52
3	1	2.0	2.8	45																		B381172	256.03	257.56	<0.005			VA05066289	1.53
4	1	2.0	3.5	60							0.1	1.0							90.0			B381173	257.56	259.08	<0.005			VA05066289	1.52
3	1	1.5	4.0	40																		B381174	259.08	260.60	<0.005			VA05066289	1.52
5	1	4.0	9.0	55							3.0											B381175	260.60	262.13	<0.005			VA05066289	1.53
																						B381176	BLANK		<0.005			VA05066289	
2	4	0.2	0.4	30																		B381177	262.13	263.65	0.01			VA05066289	1.52
1	1	2.0	2.0	80									0.2									B381178	263.65	265.18	<0.005			VA05066289	1.53
1	1	6.0	6.0	80	30						1.0		0.1									B381179	265.18	266.70	<0.005			VA05066289	1.52
3	1	3.0	7.0	70									1.0						90.0			B381180	266.70	268.22	<0.005			VA05066289	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-295C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1022m

BEARING: 000 | DIP: -50°

DATE STARTED: 15-Jul-05 | DATE COMPLETED: 20-Jul-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459755 NORTHING: 7099152

COORD SYSTEM: NAD 83: EASTING: 459636 NORTHING: 7099337

NAD 27 (CORRECTED for historic grid): EASTING: 459725 NORTHING: 7099162

SECTION LINE(historic grid): 459725E

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden: 35.05m

Deviation:

Casing: 33.53m

Core Size: HQ & NQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
35.05	281.94	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B382387 to B382439

Requisition #: MASP448STRGOL.05Q Date Shipped: 22-Jul-05

Lab Record #: VA05062471 Date Received: 17-Jul-05

Sample Sequence: B382440 to B382617

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Jul-05

Lab Record #: VA05064957 Date Received: 8-Aug-05

Duplicates:	B382402, B382422, B382442, B382462, B382482, B382502, B382522, B382542, B382562, B382582, B382602,
Preparation Duplicate/ Check Assay:	B382409, B382429, B382449, B382469, B382489, B382509, B382529, B382549, B382569, B382589, B382609,
Standards:	B382410(5E), B382430(6F), B382450(7G), B382470(2B), B382490(3C), B382510(4D), B382530(1A), B382550(5E), B382570(6F), B382590(7G), B382610(3C)
Blanks:	B382396, B382416, B382436, B382456, B382476, B382496, B382516, B382536, B382556, B382576, B382596, B382616

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
75.0	334.0	-53.3	000.0	001.0
180.0	334.9	-51.1	000.9	001.9
210.0	336.2	-48.6	002.2	003.2
281.9	338.2	-46.0	004.2	005.2

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Switched from HQ to NQ at 66.63m.

DRILL LOG LEGEND - P1		DATE: July 15-20, 2006 PAGE 1 of 14									
DRILL HOLE # : DG05-295C		FeOx: 0 = Unoxidized, 5 = Intensely Ox'd		Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered						Carbonate: 0 = No Effervescence, 5 = Strong Effervescence	
Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 65; QTZ = 90; FZ = 92; SZ = 93											
	GEOLOGICAL DESCRIPTION				ROCK (Alteration)						
UNIT CODE	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other	
-1	0.00 - 33.53	0.00	33.53	no recovery							
10	33.53 - 281.94	33.53	48.50	GND: v. broken up to crumbly GND. Limonite covers fracture faces and is pervasive through ~50% of rock. 14cm clay-gravel seam at 42.60m. Recovery is v. poor (ave ~40%).	3	0	0	1	2		
10		48.50	59.44	GND: Sand to gravel texture over 90% of section. Med yellowish brown. From 57.01 to 59.44m, rock is ox'd pervasively to sand/clay texture. Variable colours w/in, due to some hematite staining to deep reddish brown, and ox'd calcite to yellow. Overall colour med to light brown. One vein visible at 59.32m, in competent section 12cm wide. No selvage visible. Recovery is poor: 40%.	5	0	0	2	3		
10		59.44	64.01	GND still highly ox'd and ~40% alt'd such that GND texture is no longer visible; from competent (80%) to clay rich (20%). Recovery improved - up to 100% (lowest: 89%).	3	1		2	2		
10		64.01	79.38	GND: At 66.63m, core size switches from HQ to NQ. GND texture preserved in competent core with excellent recovery. Limonite throughout, in veinlets and in GND matrix. (Limonite contains carbonate.)	3				2		
10		79.38	89.92	GND: Unalt'd GND separated by wide chl/cb selvages around qtz veins, carb veins and sulph veins. V minor limonite staining in patches throughout rock	1	1	2		2		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.6	1.8	50		2.0	q	3	3	2.0								5.0				B382387	33.53	35.05	0.046			VA05062471	1.52
5	1	1.0	3.5	45	30	2.0	q/cb	2	4	5.0	5.0		20.0					1.0				B382388	35.05	36.58	0.084			VA05062471	1.53
5	1	1.0	3.5	45	30	2.0	q/cb	2	4	5.0	5.0		20.0					1.0				B382389	35.05	36.58	0.109	PD/CA		VA05062471	1.53
																						B382390	STANDARD 1A		0.764	1A		VA05062471	
0																						B382391	36.58	38.10	0.094			VA05062471	1.52
1	1	0.5	0.5	45		1.0	q/cb	1	3				15.0						2.0			B382392	38.10	39.62	0.026			VA05062471	1.52
0																						B382393	39.62	41.15	0.042			VA05062471	1.53
0																						B382394	41.15	42.67	0.102			VA05062471	1.52
1	1	1.0	1.0	30		1.5	q	1	3				5.0									B382395	42.67	44.20	0.036			VA05062471	1.53
																						B382396	BLANK		<0.005			VA05062471	
																						B382397	44.20	45.72	0.044			VA05062471	1.52
2	1	0.5	1.0	65		10.0	q	3	4	2.0									5.0			B382398	45.72	47.24	0.272			VA05062471	1.52
0																						B382399	47.24	48.50	0.044			VA05062471	1.26
0																						B382400	48.50	48.77	0.166			VA05062471	0.27
2	1	0.5	1.0	60		2.0	q/cb	4,3	3	8.0								5.0				B382401	48.77	50.29	0.029			VA05062471	1.52
2	1	0.5	1.0	60		2.0	q/cb	4,3	3	8.0								5.0				B382402	48.77	50.29	0.025	DUP		VA05062471	1.52
																						B382403	50.29	51.82	0.161			VA05062471	1.53
																						B382404	51.82	53.34	0.125			VA05062471	1.52
																						B382405	53.34	54.86	0.086			VA05062471	1.52
																						B382406	54.86	56.39	0.023			VA05062471	1.53
																						B382407	56.39	57.91	0.159			VA05062471	1.52
1	1	1.0	1.0							2.0								5.0				B382408	57.91	59.44	0.165		section all alt'd	VA05062471	1.53
1	1	1.0	1.0							2.0												B382409	57.91	59.44	0.149	PD/CA		VA05062471	1.53
																						B382410	STANDARD 5E		1.38	5E		VA05062471	
5	1	1.0	2.5	40	20					2.0	8.0							4.0				B382411	59.44	60.96	0.22			VA05062471	1.52
3	1	1.0	3.0	20		1.0	q/cb	3	4	12.0								4.0				B382412	60.96	62.48	0.169			VA05062471	1.52
1	1	1.0	1.0	40		5.0	q	2	3	0.1								4.0				B382413	62.48	64.01	0.076			VA05062471	1.53
1	4	1.0	1.0	45		20.0	cb	3	3																				
5	1	1.5	5.0	40	15	2.0	q/cb	2	3	20.0								5.0				B382414	64.01	65.53	0.075			VA05062471	1.52
2	1	3.2	4.0	15	60	1.0	q	2	3	3.0								5.0				B382415	65.53	66.63	0.067			VA05062471	1.10
																						B382416	BLANK		<0.005			VA05062471	
3	1	0.5	1.5	50		3.0	q/cb	2	3	5.0								5.0				B382417	66.63	67.89	0.329			VA05062471	1.26
2	3	0.4	0.4	135		1.0	q/cb	3	3	15.0								4.0				B382418	67.89	68.58	0.302			VA05062471	0.69
9	3	0.8	3.0	50	30	1.0	q/cb	3	2	4.0			1.0					4.0				B382419	68.58	69.66	0.053			VA05062471	1.08
1	1	1.0	1.0	20		1.0	q	4	1	2.0								5.0				B382420	69.66	70.66	0.077			VA05062471	1.00
1	6	0.4	0.4	35		2.0	q/cb	3	2	30.0			60.0					3.0											
1	6	0.4	0.4	45		1.5	q/cb	2	1	20.0			40.0					3.0				B382421	70.66	71.63	0.032			VA05062471	0.97
1	1	1.4	1.4	50		2.0	q/cb	3	3	2.0								4.0											
1	1	1.4	1.4	50		2.0	q/cb	3	3	2.0												B382422	70.66	71.63	0.056	DUP		VA05062471	0.97
4	1	12.0	15.0	50	30	1.0	q	2	2	7.0								5.0				B382423	71.63	73.22	0.086			VA05062471	1.59
3	3	0.3	0.9	35	80	4.0	q/cb/chl	3	1	0.1								5.0				B382424	73.22	74.68	0.08			VA05062471	1.46
1	1	1.3	1.3	20		0.5	q/cb	2	2	2.0			0.1					5.0											
7	1	1.0	7.0	40	60	2.0	q	2	3	5.0								5.0				B382425	74.68	76.21	0.043			VA05062471	1.53
5	1	1.0	5.0	20	40	2.0	q/chl	2	2	1.0	1.0		10.0					5.0				B382426	76.21	77.72	0.047			VA05062471	1.51
1	4	0.3	0.3	40		10.0	q/chl	4	2	20.0								5.0											
4	4	0.2	0.8	45	10	1.0	chl/cb	3	1	3.0								5.0				B382427	77.72	78.20	0.02			VA05062471	0.48
4	1	1.0	4.0	35		2.0	q/chl	2	1	5.0			10.0					5.0				B382428	78.20	79.38	0.112			VA05062471	1.18
3	4	0.2	0.6	15	50	6.0	cb/chl	3	1																				
3	4	0.2	0.6	15	50	6.0	cb/chl	3	1													B382429	78.20	79.38	0.274	PD/CA		VA05062471	1.18
																						B382430	STANDARD 6F		NSS	6F		VA05062471	
6	1	2.0	5.0	45		20.0	cb/chl	4	1		5.0		10.0					1.0				B382431	79.38	80.77	0.166			VA05062471	1.39
3	1	0.7	1.4	45		1.0	cb/chl	4	1		5.0		10.0					1.0				B382432	80.77	82.29	0.098		carb/sulph/qtz vein	VA05062471	1.52
3	4	1.0	1.4	45	60	40.0	cb/s	3	1	50.0								5.0											
							q/chl	2																					
6	1	2.0	5.4	60	25	1.0	q	3	1	5.0								2.0				B382433	82.29	83.82	0.647			VA05062471	1.53
							cb/chl	1																					
5	1	3.0	6.5	40		2.0	cb/chl	3	1		2.0		5.0					1.0	1.0			B382434	83.82	85.34	0.045			VA05062471	1.52
							q	2																					
2	1	0.6	1.0	40	10	1.0	q	3	1		5.0		5.0									B382435	85.34	86.87	0.068			VA05062471	1.53

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 3 of 14		
DRILL HOLE # : DG05-295C	FeOx: 0 = Unoxidized; 5 = Intensely Ox'd	Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered	Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		89.92	99.06	GND: silicified, aphanitic rock. Appearance is uniform dark grey with low-to-high angle carb veinlets, only 1mm wide, with ~1cm selvages. Few well-defined qtz veins	1		2		2	
10		99.06	106.68	GND: Chloritized/ ser'd GND with preserved texture.	1	2	3	1	2	
10		111.25	114.30	GND: v. crumbly dark grey GND. Ave cobble size is ~4cm in diameter. 2.5cm, pure qtz pebbles, two qtz veins in situ.			2	1	1	
10		114.30	126.49	GND: unalt'd GND separated by wide chlorite and carbonate-rich selvages. Sample actually only contains ~10-15% unalt'd GND due to the large amount of veins, and their large selvages (>30cm). Selvage at 115.50m hits unalt'd GND at 30° to CA (attributed to carb-qtz veins); veins are qtz, qtz-carb, and sulphide. Veins are called qtz-carb ("3") if carb content is greater than qtz content. Similarly, 'sulphide' veins ("6") contain more sulphides than anything else.		2	3	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar,, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	3	1.0	2.0	30		1.0	q/cb	4	1	10.0								5.0											
1	4	0.4	0.4	35		6.0	q/cb	4	2	1.0			3.0					5.0											
																						B382436	BLANK		<0.005			VA05062471	
5	4	0.3	1.0	25	120	1.0	q/cb	3			10.0		5.0					1.0				B382437	86.87	88.40	0.008			VA05062471	1.53
3	1	0.5	1.5	15	30					10.0			7.0					2.0	1.0			B382438	88.40	89.92	0.052		qtz incorp. into selvage of carb/sulph veins	VA05062471	1.52
3	4	0.6	1.0	35	80	30.0	q/chl	4	1	10.0								5.0											
3	3	1.0	1.4	45		1.0	cb/chl	4	1	20.0								5.0				B382439	89.92	91.45	0.029			VA05062471	1.53
1	4	0.2	0.2			2.0	cb	2														B382440	91.45	92.96	0.021		pieces (no angle)	VA05064957	1.51
1	1	0.5	0.5	10		2.0	q/chl	4		8.0								4.0				B382441	92.96	94.49	0.023			VA05064957	1.53
							cb	1																					
1	1	0.5	0.5	10		2.0	q/chl	4		8.0								4.0				B382442	92.96	94.49	0.022	DUP		VA05064957	1.53
1	1	1.0	1.0	30		2.0	q/chl	4		8.0	15.0							3.0				B382443	94.49	96.01	0.025			VA05064957	1.52
							cb	2																					
2	4	0.2	0.4	45	10	0.5	cb	3	1				4.0						1.0										
2	4	0.2	0.4	30	20	0.5	cb	3		0.1								4.0				B382444	96.01	97.54	0.005			VA05064957	1.53
3	1	1.0	2.5	25	50	4.0	chl/cb	4	1	5.0	5.0							4.0				B382445	97.54	99.06	0.2			VA05064957	1.52
							q	3																					
1	3	1.0	1.0	40		1.5	q/chl	3			15.0							1.0				B382446	99.06	100.58	0.039			VA05064957	1.52
							cb	3																					
3	1	1.2	2.7	15	5	2.0	q/chl	4	1	10.0			15.0	5.0								B382447	100.58	102.11	0.796			VA05064957	1.53
							cb	2																					
4	1	0.5	2.0	20	45	4.0	q/chl	3		5.0			10.0									B382448	102.11	103.64	6.44			VA05064957	1.53
4	1	0.5	2.0	20	45	4.0	q/chl	3		5.0			10.0									B382449	102.11	103.64	7.86	PD/CA		VA05064957	1.53
																						B382450	STANDARD 7G		4.36	7G		VA05064957	
2	3	1.0	1.4	45	20	3.0	cb/chl	3					10.0						3.0			B382451	103.64	105.16	0.109			VA05064957	1.52
							q	2																					
4	1	1.0	3.5	45		1.0	q/chl/cb	2	1	3.0	8.0		0.1					1.0	3.0			B382452	105.16	106.68	0.105			VA05064957	1.52
3	3	0.5	1.5	30		1.0	cb	2					2.0																
4	1	1.0	2.5	40		2.0	q/chl/cb	3														B382453	106.68	108.20	0.016			VA05064957	1.52
1	3	5.0	5.0			1.0	cb	3			10.0							1.0											
2	3	2.0	3.0	35		3.0	chl/cb	3	1		5.0		3.0					1.0	2.0			B382454	108.20	109.73	0.013			VA05064957	1.53
							q	1																					
2	1	1.0	2.0	25		1.5	q	4					1.0						4.0			B382455	109.73	111.25	0.014			VA05064957	1.52
2	3	0.3	0.6	15	50	4.0	q/ch	3		10.0	10.0							2.0											
							cb	2																					
																						B382456	BLANK		<0.005			VA05064957	
5	1	2.5	8.0	50						2.0			3.0					5.0				B382457	111.25	112.77	0.089		most qtz in pieces	VA05064957	1.52
1	1	0.5	0.5	40							3.0											B382458	112.77	114.30	0.159			VA05064957	1.53
1	4	0.2	0.2	145																									
1	1	0.4	0.4	50		65.0	cb/chl	4	1	0.1								5.0				B382459	114.30	115.83	0.021		selvage for all veins	VA05064957	1.53
							q/s	2																					
2	3	0.5	1.0	30						5.0								5.0											
7	1	1.3	7.0	35	45	20.0	cb/chl	3			8.0											B382460	115.83	117.35	0.193			VA05064957	1.52
							q/s	2																					
2	3	0.2	0.4	140		1.0	cb	2		0.1								5.0											
7	1	1.2	6.0	30	40	4.0	chl/cb	4			10.0											B382461	117.35	118.87	0.07			VA05064957	1.52
							q/s	1																					
7	1	1.2	6.0	30	40	4.0	chl/cb	4			10.0											B382462	117.35	118.87	0.139	DUP		VA05064957	1.52
4	4	0.2	0.8	150		1.0	cb	2		0.1								5.0											
5	1	1.0	4.0	40	10	150.0	cb/chl	3		15.0	8.0		2.0			0.1						B382463	118.87	120.40	0.064		selvage for both vein types	VA05064957	1.53
							q/s	3,1																					
5	3	1.5	3.5	110	60					20.0								2.0											
8	1	1.0	6.0	30	40	25.0	cb/chl	3	1	10.0	5.0	1.0						5.0				B382464	120.40	121.92	0.175		ox'n of carb	VA05064957	1.52
							q/s	2																					
1	6	1.0	1.0	50		14.0	q/chl/cb	3		90.0			10.0					5.0											
3	4	1.0	2.0	20	60	6.0	cb/chl	4	1																				
							q/s	1																					
3	3	1.0	3.0	40	30	10.0	cb/q	3					10.0						2.0			B382465	121.92	123.44	0.036		from clay to competent carb	VA05064957	1.52
2	1	1.0	2.0	30		30.0	cb/chl	4		3.0	5.0		5.0					3.0											
							q/s	2																					

DRILL HOLE # : DG05-295C

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		126.49	132.99	GND: First metre is gradation into aphanitic, pale greenish grey to dark grey, uniform texture, except veinlets of carbonate at 20° and 140° to CA (approx 40 per metre). Weak slickensides on fracture faces. Carb-qtz veins appear 'smeared' out, with both qtz and carb in elongate, thin lenses.	1	1	3	2	2	
10		132.99	140.21	GND: unalt'd GND separated by chl'd and carb'd selvages, not as wide as before, up to 20cm in width. Section is ~60% unalt'd GND, and 40% alt'd; all is solid and competent with v good recovery. Qtz veins have much smaller, silicified selvages while carb veins have larger carb'd and chl'd selvages.		1	2		2	
10		140.21	141.73	GND: One sample with intense chl and carb alt'n. Sulphides in veinlets accumulated in zone from 140.75 to 141.05m, with carbonate in clear, large veins. Within selvage, carbonate forms 1-4mm grains with irregular shape but stand out amongst chl'd GND.			4	1	3	
10		141.73	152.41	GND: A lot less carb here. Unalt'd GND with qtz veins. Carb-qtz veins contain more and larger po and aspy than qtz veins. At 146.10 to 146.30m, fracture face at 5° to CA shows strong slickensides in chl and qtz and calcite to 50°.		1	1		1	
10		152.41	155.49	GND: Dark grey, aphanitic, silicified GND. Only 1mm bt preserved. Carb'd, chl'd selvages surround qtz/carb/sulph veins (up to 2cm), and veinlets (up to 1cm). One vein of unalt'd GND intrudes this aphanitic silicified rock. 2.4cm wide, at 15° to CA, at 154.30m.	1	1	2		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 16-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	4	1.0	2.3	20	30	10.0	cb/chl	4		0.1								5.0				B382466	123.44	124.97	**1.215**			VA05064957	1.53
2	3	0.5	1.0	50		10.0	q/cb	3		20.0								1.0											
							chl/s	3																					
5	1	1.0	5.0	40		6.0	cb/chl	4					0.1						1.0			B382467	124.97	126.49	**0.075**			VA05064957	1.52
							q	1																					
3	3	18.0	20.0	50		10.0	q/chl/cb	4		5.0			3.0					1.0											
2	4	0.5	1.0	70	20	4.0	cb	3														B382468	126.49	128.01	**0.464**			VA05064957	1.52
2	3	8.0	9.0	50	70	10.0	q/cb	3		15.0	3.0							4.0											
3	1	1.0	3.0	55	50	2.0	q/chl	4		10.0	5.0		5.0					2.0	2.0										
3	1	1.0	3.0	55	50	2.0	q/chl	4		10.0	5.0		5.0					2.0	2.0			B382469	126.49	128.01	**0.429**	PD/CA		VA05064957	1.52
																						B382470	STANDARD 2B		**3.42**	2B		VA05064957	
9	3	0.3	1.5	40	70	1.0	q/cb	1		2.0								5.0				B382471	128.01	129.54	**0.233**		veinlets btwn 40° and 70°	VA05064957	1.53
2	6	0.3	0.5	85		1.0	q	3		100.0								5.0											
2	1	1.0	2.0	45		1.0	q/cb	3		0.1								5.0				B382472	129.54	131.07	**0.105**			VA05064957	1.53
2	3	1.0	2.0	60		2.0	cb	2		1.0								5.0											
1	6	0.4	0.4	30		2.0	cb/chl	3	1	100.0								5.0											
0																						B382473	131.07	132.59	**0.583**		~40 carb veinlets (random orientations)	VA05064957	1.52
3	1	0.8	2.4	40		8.0	q/chl	4		2.0	12.0							5.0				B382474	132.59	132.99	**0.342**		ox'd py, not po	VA05064957	0.40
							cb	1																			carb veinlets continue (<1mm), 80-90° to CA		
3	3	0.2	0.5	40	120	2.0	cb/chl	4					2.0									B382475	132.99	134.32	**0.062**			VA05064957	1.33
1	1	1.0	1.0	15		1.0	q	2		1.0	8.0		4.0						4.0										
																						B382476	BLANK		**0.006**			VA05064957	
9	1	0.6	3.0	40	25	1.0	q/chl	3,2														B382477	134.32	135.64	**0.083**		late carb veinlets through	VA05064957	1.32
							cb	1			15.0							1.0											
3	1	0.5	1.5	30		3.0	q/chl	3	1		12.0		0.1					1.0				B382478	135.64	136.39	**0.097**			VA05064957	0.75
							cb	3																					
5	1	1.3	4.5	30	50	3.0	q/chl	5	1		12.0		6.0					1.0				B382479	136.39	137.15	**0.032**			VA05064957	0.76
1	4	0.2	0.2	85		8.0	cb	4																					
5	1	1.0	3.9	35	15	2.0	q/chl	4			15.0		2.0									B382480	137.15	137.90	**0.054**		copper-coloured po	VA05064957	0.75
4	1	1.0	3.0			2.0	q/chl	4														B382481	137.90	138.68	**0.148**			VA05064957	0.78
2	4	0.4	0.8			20.0	cb	3																					
2	4	0.4	0.8			20.0	cb	3														B382482	137.90	138.68	**0.048**	DUP		VA05064957	0.78
5	1	1.2	3.2	40	50	3.0	q/chl/cb	4			8.0	4.0	4.0									B382483	138.68	139.58	**0.202**			VA05064957	0.90
4	4	0.2	0.8	60	70	10.0	cb	4														B382484	139.58	140.21	**0.356**			VA05064957	0.63
4	6	3.0	6.0	35		100.0	cb/chl	4		100.0								4.0				B382485	140.21	141.73	**0.127**			VA05064957	1.52
2	4	2.0	3.5	40																									
3	1	1.1	3.0	35		2.0	q/cb	2					4.0																
7	1	1.0	5.0	30	60	2.0	q/cb	3		3.0	5.0		6.0						2.0			B382486	141.73	143.26	**0.015**			VA05064957	1.53
2	1	0.6	1.8	35		2.0	q/chl	3		1.0			3.0									B382487	143.26	144.78	**0.04**			VA05064957	1.52
4	3	2.0	5.0	40	30	10.0	cb/s	3	1	2.0	20.0		2.0																
2	1	0.5	1.0	30	35	1.0	q	3			3.0		2.0									B382488	144.78	146.30	**0.034**			VA05064957	1.52
1	3	0.7	0.7	40		0.5	q/cb	3			10.0		2.0						2.0										
1	3	0.7	0.7	40		0.5	q/cb	3			10.0		2.0						2.0			B382489	144.78	146.30	**0.021**	PD/CA		VA05064957	1.52
																						B382490	STANDARD 3C		**0.094**	3C		VA05064957	
6	1	1.0	3.0	35	40	1.0	q	3			15.0											B382491	146.30	147.83	**0.172**			VA05064957	1.53
3	1	0.6	2.4	50		0.5	q	3			5.0		15.0						4.0			B382492	147.83	149.38	**0.025**			VA05064957	1.55
2	3	0.5	1.0	40		1.5	cb/chl	4			4.0		10.0						3.0										
	4	0.2	0.2	70																									
3	1	0.4	1.2	35		1.0	q/cb	2			20.0											B382493	149.38	150.88	**0.071**		6 carb veinlets at ~35° to CA	VA05064957	1.50
6	1	1.0	4.0	40		15.0	q/cb	4		10.0	5.0							5.0				B382494	150.88	152.41	**0.089**		carb increase in selvages	VA05064957	1.53
							chl	3																					
1	1	0.3	0.3	40		2.0	q/chl	4					0.1									B382495	152.41	153.92	**0.025**			VA05064957	1.51
							cb/chl	2																					
																						B382496	BLANK		**<0.005**			VA05064957	
1	GND	2.5	2.5	40																		B382497	153.92	154.62	**0.019**			VA05064957	0.70
1	1	0.3	0.3	45		2.0	q/chl	3					5.0																

DRILL LOG LEGEND P1	DATE: July 15-20, 2006 PAGE 7 of 14	
DRILL HOLE # : DG05-295C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		155.49	164.66	GND: Back to unalt'd GND w/ small qtz veins with po. Carb in selvages and a few veinlets		1	1		2	
10		164.59	177.90	GND: Section is 40% carbonate-rich competent GND. Selvages around carb/qtz/sulph veins and veinlets. GND texture preserved throughout. Sulphide veins in first sample - 164.59 to 166.12m indicate a sense of shear, dextral if vein is to 40°. Shear zone is 15cm wide, actual.		1	1		3	
10		177.90	182.62	GND: 90% alt'd with carb and chl but still competent with 100% recovery. Actual carbonate veins appear: approx 2 per metre and 0.5 to 2cm wide		2	4		3	
10		182.62	192.03	GND: 60% unalt'd GND. Carbonate veins and qtz veins w/ po continue, but fewer and smaller sulphide veins (explains less alt'n). One 4cm carb vein at 185.25m contains large, brecciated clasts of chl'd GND 1-4cm in diameter.	1		2		2	

DRILL LOG LEGEND P2

Selvages 0 = No Alteration 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides 5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3	0.4	0.8	30		3.0	q/cb	3			20.0	0.1	10.0					1.0				B382498	154.62	155.49	**0.114**			VA05064957	0.87
4	1	1.0	2.2	40		1.0	q	3			5.0		5.0					4.0	3.0			B382499	155.49	156.97	**0.05**			VA05064957	1.48
5	1	1.0	4.0	40	15	10.0	q/cb	3	1		10.0		5.0						3.0			B382500	156.97	158.49	**0.032**		carb ox'n	VA05064957	1.52
3	1	1.0	3.0	40	30	4.0	q	4			7.0		3.0						3.0			B382501	158.49	160.02	**0.048**			VA05064957	1.53
3	1	1.0	3.0	40	30	4.0	q	4			7.0		3.0						3.0			B382502	158.49	160.02	**0.023**	DUP		VA05064957	1.53
2	1	1.0	1.5	40		2.0	q	4	1				5.0						1.0			B382503	160.02	161.56	**0.179**			VA05064957	1.54
5	3	1.2	3.8	35	50	2.0	q/cb	4			5.0		20.0																
3	1	1.0	2.0	15	40	2.0	q/chl	3			8.0		4.0						1.0			B382504	161.56	163.07	**0.108**			VA05064957	1.51
1	6	0.3	0.3	70		15.0	cb/chl	3,1		100.0								5.0											
4	3	0.5	1.8	35		2.0	cb/chl	2			10.0		2.0					2.0	2.0										
6	1	1.4	5.6	50	25	8.0	cb/chl	4	1		6.0							3.0				B382505	163.07	164.59	**0.367**			VA05064957	1.52
1	6	0.8	0.8	60		4.0	cb	2	2	100.0								5.0											
5	6	0.4	1.4	30	40	20.0	cb/q	4		80.0	15.0				5.0			4.0				B382506	164.59	166.12	**0.086**			VA05064957	1.53
							chl	1																					
2	1	1.0	1.4	30		3.0	q/chl	4			5.0		5.0									B382507	166.12	167.69	**0.15**			VA05064957	1.57
3	3	1.5	3.2	40		4.0	q/cb	4			5.0		15.0					1.0	1.0										
							chl	2																					
5	1	1.5	3.5	35		20.0	cb/chl	4			10.0		5.0					3.0				B382508	167.69	169.16	**0.06**			VA05064957	1.47
							q	2																					
5	1	1.5	3.5	35		20.0	cb/chl	4			10.0		5.0					3.0				B382509	167.69	169.16	**0.064**	PD/CA		VA05064957	1.47
																						B382510	STANDARD 4D		**0.401**	4D		VA05064957	
3	3	0.3	0.9	40		4.0	q/cb	4		0.1								5.0				B382511	169.16	169.96	**0.062**			VA05064957	0.80
1	1	1.0	1.0	45		10.0	cb/chl	4			20.0		15.0						1.0										-
2	1	0.6	1.2	45		2.0	q/cb	4			7.0		1.0					2.0	3.0			B382512	169.96	170.64	**0.522**			VA05064957	0.68
3	3	0.5	0.9	25	40	2.0	cb/chl	3		0.1								5.0											
5	1	1.0	5.0	30	50	6.0	cb/q	4			10.0		5.0						1.0			B382513	170.61	172.21	**0.272**			VA05064957	1.60
							chl	1																					
3	4	0.3	0.8	5	20	3.0	cb	3		0.1								5.0											
3	1	1.2	1.8	30		10.0	cb/q	4	1		15.0	1.0	8.0						3.0			B382514	172.21	173.74	**0.067**			VA05064957	1.53
							chl	1																					
2	3	0.4	0.7	45		2.0	cb/chl	3			10.0	1.0																	
3	1	9.0	11.0	70		25.0	cb/chl	5,4	1	15.0								3.0				B382515	173.74	175.26	**0.164**			VA05064957	1.52
																						B382516	BLANK		**<0.005**			VA05064957	
5	1	3.0	6.0	35	70	2.0	q	4														B382517	175.26	176.78	**0.096**		sulph w/ carb	VA05064957	1.52
						10.0	cb/chl	3																			numerous carb veinlets w/ 1cm selvages		
2	6	0.7	1.4	25	80	8.0	cb/chl	4		5.0			3.0					2.0											
4	1	1.0	2.5	50		2.0	cb/chl	3			35.0											B382518	176.78	177.90	**0.072**			VA05064957	1.12
							q	3																					
1	3	0.2	0.2	10		3.0	chl/cb	3		5.0			3.0					2.0											
4	1	1.0	4.0	60	70	10.0	cb/chl	5														B382519	177.90	178.31	**0.056**		one w/ carb	VA05064957	0.41
3	6	0.4				1.0				100.0								2.0											
3	4	0.6	1.5	30		40.0	chl/cb	5		10.0		2.0						5.0				B382520	178.31	179.84	**0.08**			VA05064957	1.53
5	1	1.5	6.5	45		5.0	q/cb	4			15.0		10.0						4.0										
							chl	2																					
4	4	1.5	2.8	30	45	20.0	q/cb/chl	5		10.0								4.0				B382521	179.84	181.36	**0.107**			VA05064957	1.52
5	1	1.0	3.5	35	60	6.0	q/chl/cb	4			6.0		4.0						3.0										
5	1	1.0	3.5	35	60	6.0	q/chl/cb	4			6.0		4.0						3.0			B382522	179.84	181.36	**0.098**	DUP		VA05064957	1.52
5	4	0.8	2.5	40	70	20.0	cb/chl	5		5.0			3.0					2.0				B382523	181.36	182.63	**0.134**			VA05064957	1.27
4	1	1.2	4.0	40		6.0	q/cb/chl	4			10.0																		
3	1	1.0	2.0	60	40	2.0	q/cb/chl	3			5.0		10.0					1.0	3.0			B382524	182.62	183.44	**0.044**			VA05064957	0.82
5	1	3.0	7.5	40		3.0	q/chl	3			5.0		15.0						4.0			B382525	183.44	184.18	**0.034**			VA05064957	0.74
7	1	3.0	8.0	55	85	15.0	cb/chl	4	1		10.0				3.0							B382526	184.18	185.42	**0.05**		carb vein w/ brecciated GND	VA05064957	1.24
2	4	4.0	5.0	60	80	8.0	q/chl	5	1	5.0								5.0											
							cb	2																					
																						B382527	185.42	186.44	**0.034**			VA05064957	1.02
4	4	0.5	2.0	70		20.0	cb/chl	5		0.1								5.0				B382528	186.44	187.45	**0.268**			VA05064957	1.01
5	1	1.0	3.5	40	60	10.0	q/cb	4			15.0		3.0						5.0										
							chl	2																					
4	4	0.5	2.0	70		20.0	cb/chl	5		0.1								5.0				B382529	186.44	187.45	**0.146**	PD/CA		VA05064957	1.01
5	1	1.0	3.5	40	60	10.0	q/cb	4			15.0		3.0						5.0										
																						B382530	STANDARD 1A		**0.875**	1A		VA05064957	

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 9 of 14	
DRILL HOLE # : DG05-295C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd **Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		192.03	196.70	GND: Zone of extreme alt'n; all silicified and chloritized, and carbonate-rich. Sulphide veins and veinlets reappear. Last sample (195.61-196.7m), contains many (7) sulphide veins, all but one are >90% ox'd py. One vein is unox'd. Massive aspy here as well, not in straight vein, but more irregular.	1	1	4		3	
10		196.70	207.27	GND: Unalt'd GND with far fewer veins			1		1	
10		207.27	220.98	GND: Increase in carbonate within GND causes rock to be crumbly and v broken up. Longest core is ~30cm, but only 2 lengths. Low-angle carbonate and qtz veins still visible in angular fragments; veins have corroded edges, so are silicifying GND - not sharp boundaries, difficult to spot (most). One qtz vein at 211.30m is 2.5cm and has ~20% sulphides: po and py. No selvage. On the surface of this vein a strong lineation appears in calcite, bt and clay-alt'd feldspars. Sample from 220.98 to 222.51m contains sulphide-rich qtz veins. At 60°, vein contains 30% massive aspy. Vein at 50° contains 15% po and 5% cpy (no aspy)		1	1	1	2	
10		220.98	224.03	GND: One sample. Chloritized section surrounding sulph-rich qtz veins and sulphide veinlets (ox'd py). Small clay alt'n due to carb.	1	1	3	1	2	
10		224.03	234.69	GND: Unalt'd, somewhat finer-grained GND. Ave mineral size is 1-2mm. Many episodes of sheeted qtz veins; some are difficult to see, others are clear, all are at similar angle (50-60°)			1		1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	1.5	4.5	25	50	10.0	q/cb	4			15.0		10.0						1.0			B382531	187.45	188.46	0.06			VA05064957	1.01
							chl	2																					
1	4	0.3	0.3	145																									
4	1	2.0	6.0	30	45	8.0	cb/q/chl	4		3.0	5.0		15.0									B382532	188.46	189.48	0.087			VA05064957	1.02
3	3	1.0	1.8	60		10.0	q/cb/chl	4		2.0								5.0				B382533	189.48	190.50	0.174			VA05064957	1.02
3	1	2.0	3.5	60	45	4.0	q/cb	3			15.0		5.0																
5	1	1.0	5.0	60		8.0	q/cb/chl	4		5.0	3.0		5.0					5.0				B382534	190.50	192.03	0.1		selvage may not be due to vein; vein may be later	VA05064957	1.53
3	1	1.5	4.0	55	25	18.0	q/cb/chl	4	1	10.0	20.0		10.0					3.0				B382535	192.03	193.55	0.13			VA05064957	1.52
3	4	1.2	2.8	60		20.0	q	4		3.0								5.0											
																						B382536	BLANK		<0.005			VA05064957	
7	1	2.0	7.5	60	50	12.0	q/cb	4	1	3.0	10.0		5.0									B382537	193.55	194.60	0.326			VA05064957	1.05
5	6	0.5	2.5	60	70	30.0	cb/chl	5	1	100.0								4.0											
5	1	1.3	4.6	35	55	20.0	cb/chl	5		1.0	10.0		5.0									B382538	194.60	195.61	0.049			VA05064957	1.01
1	6	0.2	0.2	55		20.0	cb/chl	4		100.0								5.0											
4	1	1.0	3.0	40	80	6.0	q/cb/chl	4		10.0			10.0									B382539	195.61	196.70	0.392			VA05064957	1.09
7	6	1.0	5.0	60	50	40.0	q/cb/chl	5		90.0			10.0					4.0											
4	4	1.0	2.0	50						3.0								5.0											
4	1	3.0	5.5	60		2.0	q/chl	1		10.0	8.0		4.0					4.0				B382540	196.70	198.17	0.141			VA05064957	1.47
4	1	5.0	5.5	65		4.0	q/chl	3					5.0						2.0			B382541	198.17	199.64	0.064			VA05064957	1.47
2	3	0.5	1.0	60		2.0	q/cb	3			10.0		3.0																
2	3	0.5	1.0	60		2.0	q/cb	3			10.0		3.0									B382542	198.17	199.64	0.098	DUP	ox'n of hematite in selvage	VA05064957	1.47
5	3	2.0	6.5	60		2.0	q/cb	3		5.0			5.0					4.0	2.0			B382543	199.64	201.17	0.301			VA05064957	1.53
6	1	1.0	5.0	60	40	2.0	q	3		10.0	4.0		3.0					5.0				B382544	201.17	202.69	0.088			VA05064957	1.52
1	6	0.3	0.3	55		1.0	q/cb	2	2	100.0								5.0											
4	1	1.0	3.5	40		1.0	q	3			5.0		10.0						4.0			B382545	202.69	204.21	0.049			VA05064957	1.52
8	1	1.0	4.5	40	60	3.0	q/chl	3			10.0		8.0						2.0			B382546	204.21	205.74	0.043			VA05064957	1.53
8	1	1.0	6.5	45	70	5.0	q/chl	3			12.0		5.0						4.0			B382547	205.74	207.27	0.058			VA05064957	1.53
3	1	4.5	5.5	60		30.0	q/chl	5		7.0	15.0		5.0					4.0				B382548	207.27	208.79	0.343			VA05064957	1.52
3	1	4.5	5.5	60		30.0	q/chl	5		7.0	15.0		5.0					4.0				B382549	207.27	208.79	0.284	PD/CA	alt'd aspy	VA05064957	1.52
																						B382550	STANDARD 5E		1.49	5E	old' vein - has euhedral 1mm aspy	VA05064957	
2	1	1.0	1.8	30		4.0	q	3					5.0						5.0			B382551	208.79	210.32	0.075		new' vein	VA05064957	1.53
4	1	1.0	3.2	30	50	1.0	q	4					1.0									B382552	210.32	211.84	0.024			VA05064957	1.52
1	1	2.5	2.5	35						3.0	20.0							3.0											
3	3	0.6	1.8	50		1.0	q/cb	3			12.0											B382553	211.84	213.36	0.133			VA05064957	1.52
2	6	0.4	0.8	50	55	1.5	q	3			65.0		20.0					1.0											
3	1	1.0	2.0	40		4.0	q/cb	4			12.0											B382554	213.36	214.88	0.214		new vein	VA05064957	1.52
3	4	1.0	1.8	20		0.5	cb	3		0.1								5.0											
1	1	2.5	2.5	60		1.0	q/cb	2			5.0		2.0						1.0			B382555	214.88	216.40	0.042		old veins	VA05064957	1.52
							chl	2																					
2	1	0.5	1.0	60		2.0	q	2			5.0																aspy in selvage; euhedral po and aspy		
																						B382556	BLANK		<0.005			VA05064957	
5	1	1.0	5.0	30	60	1.5	q/cb	4					2.0									B382557	216.40	217.93	0.035			VA05064957	1.53
1	6	0.5	0.5	40		4.0	q	4		15.0	65.0		5.0					4.0											
4	1	1.0	2.5	60		1.0	q/cb	3			8.0		5.0									B382558	217.93	218.68	0.977		one sulph ox'd, one not	VA05064957	0.75
3	1	2.0	4.0	60		4.0	q	4			20.0							1.0				B382559	218.68	219.46	0.226			VA05064957	0.78
4	1	0.5	2.0	65		2.0	q	4			30.0											B382560	219.46	220.26	0.675		aspy in selvages	VA05064957	0.80
2	6	0.5	1.0	65		35.0	cb/chl	4		100.0								2.0											
4	1	1.0	4.0	40		5.0	q/chl	3			5.0		6.0									B382561	220.26	220.98	1.35		aspy and po in different veins	VA05064957	0.72
4	1	1.0	4.0	40		5.0	q/chl	3			5.0		6.0									B382562	220.26	220.98	1.18	DUP	ox'd py at margins of qtz veins	VA05064957	0.72
6	1	2.0	8.5	60		2.0	q/chl	3			15.0	5.0	30.0									B382563	220.98	222.51	0.247			VA05064957	1.53
4	1	2.0	5.5	60		20.0	q/chl	2		15.0								3.0				B382564	222.51	224.03	0.093			VA05064957	1.52
2	6	0.3	0.5	50		40.0	chl/cb	4,2		100.0								4.0											
6	1	1.0	5.5	50	60	1.0	q/cb	3			10.0	1.0										B382565	224.03	225.55	0.176			VA05064957	1.52
							chl	1																					
1	4	0.4	0.4	25						1.0								5.0											

DRILL LOG LEGEND P1	DATE: July 15-20, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-295C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		234.69	236.22	GND: Concentration of sulphide veinlets (ox'd py) within carbonate-rich, crumbly GND	2		1	1	4	
10		236.22	245.36	GND: Highly alt'd section - carb-infused and chloritized. Sulphide vein(let)s continue, approx 4 per metre. Sample from 239.09 to 239.39m is one 21cm qtz vein with only one preserved selvage (upper). Lenses of sulphide within are up to 1cm wide. Diamagnetism of these lenses indicates presence of bismuthinite (but not visible).	3	1	2	1	3	
10		245.36	251.46	GND: Fine-grained unalt'd GND w/ minor sheeted qtz veins and minor carb alt'n.					1	
10		251.46	254.51	GND: Carbonate appears in veins; result is minor carb alt'n over 50% of section. One carbonate vein (1.3cm wide) at 252.95m has 24cm chl'd/carb'd selvage but sulphides are not prominent in carb'd section. More po (nice, large grains), in qtz veins with irregular edges.	1	1	1	1	1	
10		254.51	260.60	GND: Coarse GND texture preserved over 30% of section. Wide chloritic and oxidized selvages around qtz veins. Rare euhedral 2mm aspy disseminated in these selvages. Massive pyrite veins (only partly ox'd) at 258.70m.	2	1	2		2	
10		260.60	263.65	GND: Highly alt'd around qtz/carb/sulph veins.	1	1	3		2	
10		263.65	266.70	GND: V minor chloritic and carbonitic alt'n around qtz/carb/sulph veins.	1		1		1	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.5	4.5	60	40	2.0	q/chl	2,1			5.0											B382566	225.55	227.08	0.097			VA05064957	1.53
6	1	1.0	4.0	30		0.5	q/cb	2			5.0		4.0					3.0				B382567	227.08	228.61	0.204			VA05064957	1.53
2	6	1.0	1.5	30		20.0	cb/chl	4,2		100.0								5.0											
3	1	3.0	5.0	35		16.0	q/cb	3			5.0							1.0				B382568	228.61	230.12	0.669			VA05064957	1.51
3	1	3.0	5.0	35		16.0	q/cb	3			5.0							1.0				B382569	228.61	230.12	0.546	PD/CA		VA05064957	1.51
																						B382570	STANDARD 6F		2.86	6F		VA05064957	
6	1	1.5	4.5	60	40	1.0	q	2			5.0		3.0									B382571	230.12	231.65	0.093			VA05064957	1.53
4	1	2.0	6.0	30		1.0	q/chl	1			10.0		1.0					1.0				B382572	231.65	233.17	0.223			VA05064957	1.52
6	1	1.0	4.5	35	70	1.0	q/cb	1		5.0	8.0							5.0				B382573	233.17	234.69	0.772			VA05064957	1.52
15	6	0.8	13.0	70		75.0	cb	4	1	100.0								5.0				B382574	234.69	235.44	4.4			VA05064957	0.75
12	6	0.4	4.5	60		78.0	cb	4	1	100.0								5.0				B382575	235.44	236.22	2.02			VA05064957	0.78
							chl	1																					
																						B382576	BLANK		<0.005			VA05064957	
2	3	1.5	3.0	70		2.0	q/cb	1			5.0											B382577	236.22	237.70	0.061			VA05064957	1.48
2	4	1.0	1.5	60		10.0	cb/chl	2		0.1								5.0											
4	1	1.0	4.0	40		2.0	q/cb	3		5.0			0.1					5.0				B382578	237.70	239.09	0.332			VA05064957	1.39
1	1	21.0	21.0	40		20.0	cb/chl	5		10.0	8.0		5.0	0.1								B382579	239.09	239.39	3.5			VA05064957	0.30
20	6	0.4	5.0	70		30.0	cb	4		100.0								5.0				B382580	239.39	240.89	0.161			VA05064957	1.50
2	3	1.0	2.0	70	2	2.0	cb/chl	4		10.0								5.0											
2	3	0.3	0.6	30		1.0	cb	3		2.0			4.0					5.0				B382581	240.89	242.32	0.134			VA05064957	1.43
2	1	1.0	2.0	20		20.0	cb/chl	4		10.0								4.0											
							s/q	2																					
2	1	1.0	2.0	20		20.0	cb/chl	4		10.0								4.0				B382582	240.89	242.32	0.114	DUP		VA05064957	1.43
3	3	1.0	3.0	40		1.0	q/chl	2		2.0								5.0				B382583	242.32	243.85	0.165			VA05064957	1.53
6	6	1.0	2.0	20	85	10.0	cb/chl	5		100.0								5.0											
2	3	1.0	2.0	40		6.0	cb/q	4		2.0								5.0				B382584	243.85	244.72	0.644			VA05064957	0.87
4	6	0.2	0.8	80		16.0	cb/chl	5		100.0								5.0											
5	1	1.0	4.5	70	120	4.0	q/chl	4,2		5.0			2.0					5.0	2.0			B382585	244.72	245.36	0.255			VA05064957	0.64
5	6	0.6	2.0	70	125	10.0	cb/chl	5		100.0								4.0											
3	1	3.5	5.5	50		8.0	cb/chl	3		5.0	10.0							1.0				B382586	245.36	246.89	0.19			VA05064957	1.53
							q/s	1																					
4	1	2.0	4.5	45		5.0	q/cb	4	1	10.0	10.0							2.0				B382587	246.89	248.41	0.322			VA05064957	1.52
3	1	1.0	3.0	50		10.0	q/chl	3		10.0			5.0					4.0	2.0			B382588	248.41	249.93	0.099			VA05064957	1.52
3	1	1.0	3.0	50		10.0	q/chl	3		10.0			5.0					4.0	2.0			B382589	248.41	249.93	0.128	PD/CA		VA05064957	1.52
																						B382590	STANDARD 7G		4.45	7G		VA05064957	
5	1	1.0	4.5	35		10.0	q/chl	3	1	3.0			5.0					5.0	2.0			B382591	249.93	251.46	0.773			VA05064957	1.53
							cb/s	2																			same selvage		
8	1	1.5	7.0	35	10	125.0	q/chl	3			6.0							3.0				B382592	251.46	252.98	0.095			VA05064957	1.52
							cb/s	2																					
8	4	0.7	2.0	65	75					8.0								5.0									qtz and carb w/ sulph		
4	1	1.0	4.0	45		1.0	q	2			10.0											B382593	252.98	254.51	0.119			VA05064957	1.53
1	4	1.3	1.3	65		24.0	cb/chl	4		5.0								5.0									all selvage		
5	1	1.0	5.0	50		3.0	q/chl	4,1			5.0											B382594	254.51	256.03	0.185			VA05064957	1.52
1	6	10.0	10.0	62		40.0	cb/chl	3	1	60.0								5.0											
3	4	1.0	2.0	50		150.0	cb/chl	4	1	5.0								5.0				B382595	256.03	257.56	0.191		aspy and py in diff. veins	VA05064957	1.53
1	6	0.5	0.5	85						100.0								5.0											
																						B382596	BLANK		<0.005			VA05064957	
3	1	3.0	6.0	50		20.0	q/chl/cb	4	1	25.0			15.0					2.0				B382597	257.56	259.09	0.13			VA05064957	1.53
1	6	0.5	0.5	70		20.0	q/chl	2		100.0								2.0											
5	1	2.0	6.0	50		30.0	cb/chl/q	3			12.0											B382598	259.09	260.60	0.544			VA05064957	1.51
2	1	1.0	2.0	30		10.0	cb/chl/q	3		10.0								4.0				B382599	260.60	262.12	0.326			VA05064957	1.52
4	3	0.5	2.0	60		30.0	cb/chl	4		5.0								5.0											
2	1	1.0	2.0	40		10.0	q/cb/chl	4		2.0	5.0											B382600	262.12	263.65	0.123			VA05064957	1.53
3	6	1.0	1.4	35		20.0	chl/cb	4		100.0								5.0											
6	1	1.0	6.0	40	50	10.0	q/chl	4			6.0	1.0										B382601	263.65	265.17	0.258			VA05064957	1.52
1	6	0.3	0.3	50		8.0	q	4		100.0								5.0											
							cb/chl	1																					
1	6	0.3	0.3	50		8.0	q	4		100.0								5.0				B382602	263.65	265.17	0.027	DUP	difficult to see	VA05064957	1.52
3	1	1.0	3.0	40	50	20.0	q/chl	4		10.0	5.0							4.0				B382603	265.17	266.70	0.554			VA05064957	1.53
2	6	0.3	0.6	40		40.0	cb/chl	5		100.0								5.0									po appears w/ bt		

DRILL LOG LEGEND P1	DATE: July 15-20, 2006 PAGE 13 of 14	
DRILL HOLE # : DG05-295C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		266.70	271.12	GND: Zone of extreme carb and chl alt'n. Rock is 90% v broken to crumbly clay texture. Overall colour is pale greenish grey	2	1	4	2	4	
10		271.42	275.84	GND: Unalt'd GND w/ small qtz veins w/ small silicified selvages. Medium grey. Only small carbonate veinlets at low angle.					1	
10		275.84	281.94	GND: More carbonate content in otherwise unalt'd GND. Causes crumbly sections, up to 40cm long. GND here is somewhat finer-grained, but minerals still visible (1-2mm).					2	
			EOH							

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Drilled July 15-20, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	1.0	1.0	30						5.0								5.0				B382604	266.70	268.23	**1.08**			VA05064957	1.53
1	6	0.5	0.5	30						100.0								5.0											
3	1	1.0	3.0	50	40	4.0	q/chl	2			10.0											B382605	268.23	269.75	**0.115**			VA05064957	1.52
1	6	0.9	0.9	60		20.0	cb/chl	4		60.0								5.0									py in 0.4cm lens		
3	1	2.0	4.5	50		4.0	q/cb	4		5.0	5.0							3.0				B382606	269.75	271.12	**0.053**			VA05064957	1.37
2	6	1.5	2.5	70		10.0	q/cb	4		60.0								5.0											
1	1	12.0	12.0	70		40.0	cb/chl	4		15.0								3.0				B382607	271.12	271.42	**0.342**			VA05064957	0.30
							q	1																					
5	1	1.0	5.0	50	85	1.0	q	3			5.0							2.0				B382608	271.42	272.80	**0.085**			VA05064957	1.38
5	1	1.0	5.0	50	85	1.0	q	3			5.0							2.0				B382609	271.42	272.80	**0.068**	PD/CA		VA05064957	1.38
																						B382610	STANDARD 3C		**0.089**	3C	alt'n to bt w/in veins	VA05064957	
4	1	1.5	4.5	30	50	1.0	q/chl	3,1			3.0											B382611	272.80	274.32	**0.397**			VA05064957	1.52
1	6	0.3	0.3	155						60.0	10.0							5.0											
4	1	1.5	5.0	45	60	2.0	q	4		10.0	5.0							4.0				B382612	274.32	275.84	**0.119**			VA05064957	1.52
3	1	1.0	3.0	35		2.0	q/chl	3			10.0		4.0					3.0	1.0			B382613	275.84	277.37	**0.068**			VA05064957	1.53
3	4	0.6	1.8	25		30.0	cb	3		10.0								5.0											
1	3	0.5	0.5	65		1.0	cb/chl	2		10.0								5.0											
5	1	1.5	5.0	60	25	2.0	q/cb	4														B382614	277.37	278.89	**0.544**			VA05064957	1.52
							b	2																					
4	4	0.5	1.2	10	35	20.0	cb	2		5.0								5.0											
5	1	2.0	4.5	30	40	5.0	cb/q	3			5.0											B382615	278.89	280.21	**0.155**			VA05064957	1.32
2	3	10.0	12.0	70		2.0	cb/chl	2		15.0	2.0							5.0									sulph vein zigzags btwn 10 and 60° (sheared).		
1	6	0.5	0.5	10	60	20.0	cb	4		50.0								5.0									po w/ bt		
																						B382616	BLANK		**<0.005**			VA05064957	
4	1	1.0	4.0	50		1.0	q	2			5.0											B382617	280.41	281.94	**0.066**			VA05064957	1.53
2	3	0.3	0.6	35		1.0	q/cb	3		5.0								5.0											
																								E.O.H.					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-296C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 916m

BEARING: 000 | DIP: -50°

DATE STARTED: 19-Jul-05 | DATE COMPLETED: 21-Jul-05

LOGGED BY: Terry Croteau

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459153 NORTHING: 7099840

COORD SYSTEM: NAD 83: EASTING: 459034 NORTHING: 7100025

NAD 27 (CORRECTED for historic grid): EASTING: 459123 NORTHING: 7099850

SECTION LINE(historic grid): 459125E

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden: 4.57m

Deviation:

Casing: 4.57m

Core Size: HQ & NQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381181 to B381238

Requisition #: MASP448STRGOL.05Q Date Shipped: 5-Aug-05

Lab Record #: VA05066350 Date Received: 12-Aug-05

Sample Sequence: B381239 to B381384

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05067824 Date Received: 12-Aug-05

Sample Sequence: B281385 to B381387

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05069644 Date Received: 21-Aug-05

Duplicates:	B381182, B381202, B381222, B381242, B381262, B381282, B381302, B381322, B381342, B381362, B381382,
Preparation Duplicate/ Check Assay:	B381189, B381209, B381229, B381249, B381269, B381289, B381309, B381329, B381349, B381369
Standards:	B381190 (2B), B381210(5E), B381230(1A), B381250(7G), B381270(3C), B381290(4D), B381210(1A), B381230(7G), B381250(6F), B381270(4D)
Blanks:	B381196, B381216, B381236, B381256, B381276, B381296, B381316, B381336, B381356, B381376

FROM	TO	LITHOLOGY
4.57	198.12	MSED (QZZ; Qtz Monzonite)

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
61.0	335.0	-48.3	001.0	002.0
121.9	338.6	-49.3	004.6	005.6
198.1	339.8	-50.4	005.8	006.8

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE:	PAGE	of 10	
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered		**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
1	0.00 - 4.57	0.00	4.57	Casing with 9% recovery. MSED and GND, likely from boulders.						
80	4.57 - 30.17			MSED - Derived from pelitic to arenaceous sediment. Foliated, may be phyllitic or carbonaceous						
		4.57	9.14	MSED - Pervasive lim and lim staining on frac faces. Core is broken and recovery is poor. Foliation difficult to determine because of broken core. Foliation @4.57m is at 30-32° TCA. @6.10m, -> 50-52°; @7.62m -> 15-20°; @7.62m -> 0.2cm aspy vein @ 60° to CA	3	2	1	1	1	
80		9.14	18.29	MSED: Same as above, but more competent with better recovery. Boudins present throughout indicating increased shear. Foliation @ 9.14m -> 25-30°; @10.67m -> 30-35°; @ 12.19m -> 35-40°; @13.72m -> 35-40°; @15.24m -> 30-35°; @16.76m -> 35-40°	3	2	1	1	1	
80		18.29	21.80	MSED - Lim continues pervasively and on frac faces. Boudins are present, but reduced in frequency. Foliation @ 18.29m -> 20-25°; @19.81m -> 35-40°; @21.34m -> 30-32°.	3	2	1	1	1	
80		21.80	24.65	Silicious MSED. Dark grey colour, pervasive lim is reduced. Foliation @ 21.80m -> 30-32° @22.86m -> 25-30° @24.38m -> 20-22° @18.29m - 1cm aspy vein @ 20° to CA, 90% aspy, 2% py	2				1	
80		24.65	30.17	MSED - Lim pervasive and on frac faces. Argillic alt'n increased. Foliation is generally at lower angles. Foliation @ 24.65m-> 35-37 @ 25.91m ->22-25° @ 27.43m -> 22-25° @28.96m -> 22-25° @28.26m - 30cm sandstone bed. Brown, oxidized, 85% qtz, 10% K-feld, Laminae @ 22-25° to CA. Contact with MSED @ 22°.	2	3	1	2	2	
12	30.17 - 32.57	30.17	32.57	GND Dyke. 40% qtz 20% plag. Grey, with pervasive lim. Frac faces are stained dark red. Euhedral aspy crystals can be found within the red staining. Veins present are small (< 0.2 cm). Uphole contact not visible. Downhole contact @ 35° to CA	3					
80	32.57 - 120.40	32.57	37.50	MSED - Dark Grey. Pervasive lim is reduced, but still prevalent on frac faces. Carb veinlets increase in number. Foliation @ 32.57m -> 35-37° @ 33.53m -> 35-37° @35.05m -> 30-32° @36.58m -> 25-30°	2	3	1	1	2	
80		37.50	45.72	Silicious MSED - Minor pervasive lim, also reduced on frac faces. Increase in number of veins as well as size and mineralization. Boudins present throughout. Foliation @37.50m -> 22-25° @38.10m -> 40-42° @39.62m -> 25-30° @41.15m -> 25-30° @42.67m -> 25-27° @44.20m -> 27-30°	1				1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B381181	0.00	4.57	0.014			VA05066350	4.57
0																						B381182	0.00	4.57	0.027	DUP		VA05066350	4.57
0																						B381183	4.57	6.10	0.022			VA05066350	1.53
0																						B381184	6.10	7.62	0.025			VA05066350	1.52
1	6	0.2	0.2	60									40.0									B381185	7.62	9.14	0.05			VA05066350	1.52
0																						B381186	9.14	10.67	0.005			VA05066350	1.53
0																						B381187	10.67	12.19	0.015			VA05066350	1.52
0																						B381188	12.19	13.72	<0.005			VA05066350	1.53
0																						B381189	12.19	13.72	<0.005	PD/CA		VA05066350	1.53
																						B381190	STANDARD 2B		3.07	2B		VA05066350	
0																						B381191	13.72	15.24	0.047			VA05066350	1.52
0																						B381192	15.24	16.76	0.008			VA05066350	1.52
2	1	2.0	3.0	30						0.1												B381193	16.76	18.29	0.005			VA05066350	1.53
2	1	2.0	4.0	30						0.1												B381194	18.29	19.81	0.022			VA05066350	1.52
1	1	0.2	0.2	30																		B381195	19.81	21.34	<0.005			VA05066350	1.53
																						B381196	BLANK		<0.005			VA05066350	
0																						B381197	21.34	21.80	0.011			VA05066350	0.46
1	6	1.0	1.0	25						2.0			60.0									B381198	21.80	22.06	0.35			VA05066350	0.26
0																						B381199	22.06	22.86	0.021			VA05066350	0.80
1	6	0.1	0.1	25																		B381200	22.86	24.38	0.007			VA05066350	1.52
0																						B381201	24.38	24.65	<0.005			VA05066350	0.27
0																						B381202	24.38	24.65	0.006	DUP		VA05066350	0.27
0																						B381203	24.65	25.91	0.006			VA05066350	1.26
1	1	2.0	2.0																			B381204	25.91	27.43	0.018		Qtz eyes	VA05066350	1.52
0																						B381205	27.43	28.96	0.148			VA05066350	1.53
2	1	0.4	0.8	40																		B381206	28.96	30.17	0.017			VA05066350	1.21
2	3	1.0	1.0	20																		B381207	30.17	30.48	0.075			VA05066350	0.31
4	6	0.1	0.4	60									40.0					70.0				B381208	30.48	32.00	0.167			VA05066350	1.52
4	6	0.1	0.4	60									40.0					70.0				B381209	30.48	32.00	0.124	PD/CA		VA05066350	1.52
																						B381210	STANDARD 5E		1.355	5E		VA05066350	
2	1	0.5	1.0	50									0.1									B381211	32.00	32.57	0.024			VA05066350	0.57
0																						B381212	32.57	33.53	0.01			VA05066350	0.96
2	1	0.2	0.4	20																		B381213	33.53	35.05	0.04			VA05066350	1.52
0																						B381214	35.05	36.58	0.008			VA05066350	1.53
1	6	0.2	0.2	65		2.0	q	4	0	3.0			0.1					90.0				B381215	36.58	37.50	0.012			VA05066350	0.92
																						B381216	BLANK		<0.005			VA05066350	
1	6	3.0	3.0	60									40.0									B381217	37.50	38.10	<0.005		Crosscuts foliation	VA05066350	0.60
3	1	0.5	0.9	40																		B381218	38.10	39.99	0.057		bt in vein	VA05066350	1.89
1	1	28.0	28.0	30									5.0									B381219	39.99	40.27	0.076		bt in vein	VA05066350	0.28
3	6	0.1	0.3	60									10.0									B381220	40.27	41.15	0.006		Crosscuts foliation	VA05066350	0.88
2	4	0.1	0.2	60																		B381221	41.15	42.67	0.032		Crosscuts foliation	VA05066350	1.52
2	4	0.1	0.2	60																		B381222	41.15	42.67	0.019	DUP		VA05066350	1.52
2	6	0.1	0.2	60		2.0	b	4	0				3.0									B381223	42.67	44.20	0.029		Aspy in selvage	VA05066350	1.53

DRILL LOG LEGEND - P1	DATE:	PAGE 3 of 10		
DRILL HOLE # : DG05-296C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		45.72	56.39	QZZ (80%) with silicious MSED (20%). MSED dark grey, purple, green, foliation difficult to see. May be silicfied hornfels. QZZ light grey, no foliation and an increase in the number and size of qtz veins. Lim staining is reduced to fracture faces only. Frac faces also contain euhedral py or aspy crystals. Foliation @ 45.72m -> 30-32°, @47.24m -> 30-32°, @48.77m -> 30-32°, @50.29m -> 25-30°, @51.82m -> 40-42°, @53.34m -> 35-40°, @54.86m -> 35-37°	1	1	1	1	1	
80		56.39	67.06	MSED (70%) dark grey with prominent foliation. QZZ (30%) associated with veins, possibly related as selvages. MSED contains diss aspy and po throughout. Foliation @65.39m -> 45-50°, @57.91m -> 45-50°, @59.44m -> 45-50°, @60.96m -> 35-40°, @62.48m -> 35-40°, @64.01m -> 45-50°, @65.53m -> 35-40°. Lim staining on frac faces reduced to 30%.	1	2	2	1	1	
80		67.06	68.58	MSED HFLS - Easily scratchable. Violet, green, grey color. Qtz veining reduced, low angle (<10°) crosscuts foliation. Diss py present. Foliation @ 30-35° to CA.	1	3	2	2	1	
80		68.58	73.57	QZZ - Light grey green color. Increase in vein frequency and size as well as sulphide content. Visible residual foliation @ 70.90m -> 30° to CA			2		1	
80		73.57	80.20	Silicious MSED. Dark grey, veining is predominantly 0.2cm qtz veins with bt selvages that contain 10-20% aspy. Trace aspy can also found between foliations. Foliation @73.57m -> 35-40°, @74.68m -> 50-52°, @76.20m -> 40-45°, @77.72m -> 40-45°, @79.25m -> 45.50°		1	1		1	
80		80.20	81.16	QZZ. Light grey, 80% qtz, no visible foliation. Veins are larger, up to 9cm, and increase in number			1		1	
		81.16	83.82	Silicious MSED. Dark grey, fewer sulphide veins than previous MSED interval. Diss aspy present after 82.30m. Foliation @81.16m -> 45-50°, @82.30m -> 35-40°, crenulated		1	1		1	
80		83.82	88.39	QZZ. Light grey. Increase in 0.2cm aspy veins as well as diss aspy. Qtz veins nearly absent. Minor lim staining on frac faces (20%).	1		1		1	
80		88.39	92.63	Silicious MSED. Dark grey, minor lim on frac faces (15%). Diss aspy present. Foliation @88.39m -> 30-35°, @89.92m -> 30-35°, @91.44m -> 30-35°. Contact with QZZ @ 30°.	1	1	1		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval						
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
3	6	0.1	0.3	60		1.0	q	4	0				3.0									B381224	44.20	45.72	0.013		Aspy in selvage /Vein Crosscuts	VA05066350	1.52
4	6	0.1	0.4	60									10.0									B381225	45.72	47.24	0.142		Crosscuts foliation	VA05066350	1.52
3	1	5.0	11.0	50	30								0.1									B381226	47.24	48.77	0.025			VA05066350	1.53
1	6	0.1	0.1	125									5.0														Crosscuts foliation		
2	6	0.1	0.2	125									5.0									B381227	48.77	50.29	0.052		Crosscuts foliation	VA05066350	1.52
3	6	0.1	0.3	125									5.0									B381228	50.29	51.82	0.411		Crosscuts foliation	VA05066350	1.53
3	6	0.1	0.3	125									5.0									B381229	50.29	51.82	0.414	PD/CA		VA05066350	1.53
																						B381230	STANDARD 1A		0.83	1A		VA05066350	
1	1	2.0	2.0	50							3.0		3.0									B381231	51.82	53.34	0.015			VA05066350	1.52
2	6	0.2	0.4	60									10.0									B381232	53.34	54.86	0.166			VA05066350	1.52
	4	0.1		15	30																	B381233	54.86	56.39	0.083		Veinlets	VA05066350	1.53
1	1	3.0	40.0							3.0	3.0											B381234	56.39	57.91	0.023			VA05066350	1.52
1	1	5.0	5.0	30							1.0		1.0									B381235	57.91	59.44	0.015			VA05066350	1.53
																						B381236	BLANK		<0.005			VA05066350	
1	6	0.5	0.5							6.0			5.0									B381237	59.44	60.96	0.099			VA05066350	1.52
3	1	1.0	3.0	10	20								0.1									B381238	60.96	62.48	0.702			VA05066350	1.52
3	1	0.1	0.3	60		1.0	b	5	0				0.1									B381239	62.48	64.01	0.022		Aspy in selvage/ crosscut fol	VA05067824	1.53
2	1	25.0	35.0	25	35								0.1									B381240	64.01	65.53	0.061			VA05067824	1.52
0																						B381241	65.53	67.06	0.026			VA05067824	1.53
0																						B381242	65.53	67.06	0.041	DUP		VA05067824	1.53
1	1	1.5	1.5	125									10.0									B381243	67.06	68.58	0.026			VA05067824	1.52
3	1	1.5	2.5	20	##						1.0	0.1										B381244	68.58	70.10	0.04			VA05067824	1.52
4	1	8.0	18.0	40									0.1					90.0				B381245	70.10	71.63	0.041			VA05067824	1.53
2	1	5.0	7.0	60									0.1									B381246	71.63	73.15	0.015			VA05067824	1.52
0																						B381247	73.15	73.57	0.013			VA05067824	0.42
1	1	1.0	1.0	55							1.0											B381248	73.57	74.68	0.005			VA05067824	1.11
1	1	1.0	1.0	55							1.0											B381249	73.57	74.68	0.005	PD/CA		VA05067824	1.11
																						B381250	STANDARD 7G		4.73	7G		VA05067824	
1	1	3.0	3.0	50							1.0											B381251	74.68	76.20	0.014			VA05067824	1.52
3	1	0.1	0.3	55		1.0	q/b	5	0				1.0									B381252	76.20	77.72	0.013		Aspy in selvage	VA05067824	1.52
1	1	1.0	1.0	55		1.0	q/b	5	0				5.0									B381253	77.72	79.25	0.081		Aspy in selvage	VA05067824	1.53
2	3	1.0	1.2	55		0.5	b	4	0				3.0									B381254	79.25	80.20	0.012			VA05067824	0.95
3	1	9.0	15.0	50		2.0	chl	2	0	0.1	0.1											B381255	80.20	81.16	0.011			VA05067824	0.96
																						B381256	BLANK		<0.005			VA05067824	
4	4	0.1	0.4	30	35																	B381257	81.16	82.30	0.035			VA05067824	1.14
4	6	0.1	0.4	60									3.0									B381258	82.30	83.82	0.013			VA05067824	1.52
5	6	0.2	0.6	60									10.0									B381259	83.82	85.34	0.034		Crosscuts foliation	VA05067824	1.52
9	6	0.2	1.0	60									10.0									B381260	85.34	86.87	0.048		Crosscuts foliation	VA05067824	1.53
3	6	0.1	0.3	60									5.0									B381261	86.87	88.39	0.073			VA05067824	1.52
3	6	0.1	0.3	60									5.0									B381262	86.87	88.39	0.084	DUP		VA05067824	1.53
2	6	0.1	0.2	60		0.2	b	4	0	1.0			1.0									B381263	88.39	89.92	0.07		Aspy in selvage	VA05067824	1.52
1	6	0.2	0.2	60		0.2	q/b	3	0				1.0									B381264	89.92	91.44	0.01			VA05067824	1.19

DRILL LOG LEGEND P1	DATE:	PAGE 5 of 10	
DRILL HOLE # : DG05-296C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		92.63	93.75	MSED: Pervasive lim present until 92.96m. Lim staining on frac faces increased (60%). 80% of veins crosscut foliation @30-32 °		1				
80		93.75	104.49	Silicious MSED. Dark grey, few qtz veins. Lim staining on fractures (60%). Foliation @93.75m >30-35°, @94.49m -> 30-35°, @96.01m -> 30-32°, @97.54m -> 25-27°, @99.06m -> 40-42°, @100.58m -> 40-42°, @102.11m -> 45-50°, @103.63m -> 35-40°. @102.11m - 12cm grey qtz vein @ 45° to CA.	1	2	1		1	
80		104.49	118.87	QZZ. Light grey to grey, very little visible foliation. Interval contains a might higher concentration of sulphides than all previous intervals. Aspy veins are dominant type, as well as py. Very few veins (10%) are quartz. @105.86m - 3cm massive aspy vein. No contact visible. Vein is broken and may be larger @106.98m - 1cm massive aspy vein + sphalerite @25° to CA @107.31m - 10cm massive sulphide vein. 25% aspy, 45% py + qtz @ 60° to CA @108.58m - 1.5cm massive aspy vein @45° to CA - 1cm sphalerite vein @45° to CA @112.50m - broken massive aspy and py vein. Core recovery is 67%, vein has a minimum size of ~10cm and may be 15-20cm or greater. No qtz present. Vein is 80% aspy, 20% py. Picture 100-0059 and 100-0060		1	1			
30		118.87	120.40	QZZ/HFLS Transition between QZZ and GND dyke. Light grey QZZ with interlayered HFLS. Diss aspy in QZZ. Foliation in HFLS @35° to CA.		2	2		1	
12	120.40 - 121.92	120.40	121.92	GND - 40% qtz, 20% plag, 15% bt, 15% hbl. Dark grey, fine grained. Contains higher than usual amounts of hbl compared to other holes. Few qtz or sulphide veins. Cb veining increased. No visible contacts with surrounding core.					1	
80	121.92 - 198.12	121.92	124.97	Silicious MSED. Dark grey. Foliation at beginning of interval @20° to CA grading to 45° after 123.44m. No indication of contact with GND		2	1	1		
80		124.97	128.64	QZZ. Light grey, with relic foliation visible @45° to CA. Sulphide veinlets crosscut, as do low angle cb veinlets (10-30° to CA)			1			
80		128.64	130.86	Silicious MSED. Dark grey. Qtz veins follow foliations, and cb veining is reduced. Foliation @128.64m -> 45-47°, @129.54m -> 40-42°		1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	6	0.2	0.2	60		0.2	b	4	0				0.1									B381265	91.44	92.63	<0.005			VA05067824	1.19
4	4	0.2	0.8	20																		B381266	92.63	93.75	<0.005			VA05067824	1.12
2	1	1.0	2.0	70								3.0	1.0									B381267	93.75	94.49	0.079		Crosscuts foliation	VA05067824	0.74
2	1	1.0	1.5	35							0.1											B381268	94.49	96.01	<0.005			VA05067824	1.52
2	1	1.0	1.5	35							0.1											B381269	94.49	96.01	0.005	PD/CA		VA05067824	1.52
																						B381270	STANDARD 3C		0.096	3C		VA05067824	
4	6	0.1	0.4	55									1.0									B381271	96.01	97.54	0.079			VA05067824	1.53
	4	0.1		30																		B381272	97.54	99.06	0.014		Veinlets	VA05067824	1.52
3	1	1.0	1.7	40							0.1											B381273	99.06	100.58	0.017			VA05067824	1.52
1	1	8.0	8.0	70									5.0						90.0			B381274	100.58	102.11	0.01			VA05067824	1.53
1	1	12.0	12.0	40									1.0									B381275	102.11	103.63	0.019			VA05067824	1.52
																						B381276	BLANK		<0.005			VA05067824	
2	4	0.1	0.2	50																		B381277	103.63	104.49	0.017			VA05067824	0.86
3	1	2.0	3.0	50																		B381278	104.49	105.16	0.005			VA05067824	0.67
0																						B381279	105.16	105.86	0.013			VA05067824	0.70
1	6	3.0	3.0							10.0			80.0									B381280	105.86	105.93	2.79			VA05067824	0.07
3	1	5.0	8.0																			B381281	105.93	106.98	0.141			VA05067824	1.05
3	1	5.0	8.0																			B381282	105.93	106.98	0.157	DUP		VA05067824	0.33
1	6	1.0	1.0	25									80.0		10.0							B381283	106.98	107.31	0.153			VA05067824	0.25
1	6	10.0	10.0	65						45.0			25.0									B381284	107.31	107.56	1.06			VA05067824	
0																						B381285	107.56	108.20	0.057			VA05067824	0.64
0																						B381286	108.20	108.58	0.165			VA05067824	0.38
2	6	1.5	2.5	45									90.0		90.0							B381287	108.58	108.80	3.31			VA05067824	0.22
1	6	0.2	0.2	70						1.0												B381288	108.80	109.73	0.052			VA05067824	0.93
1	6	0.2	0.2	70						1.0												B381289	108.80	109.73	0.049	PD/CA		VA05067824	0.93
																						B381290	STANDARD 4D		0.452	4D		VA05067824	1.25
11	4	0.2	2.2	70	5																	B381291	109.73	111.25	0.037			VA05067824	0.10
1	6	0.2	0.2	60									10.0									B381292	111.25	112.50	0.108			VA05067824	1.70
1	6									20.0			80.0									B381293	112.50	112.60	3.53			VA05067824	1.52
5	4	0.2	1.0	55									5.0		5.0							B381294	112.60	114.30	0.074			VA05067824	1.70
3	1	2.0	3.0	30						1.0								90.0				B381295	114.30	115.82	0.005			VA05067824	1.52
																						B381296	BLANK		<0.005			VA05067824	
3	1	4.0	7.0	10	45					1.0			1.0									B381297	115.82	117.35	<0.005			VA05067824	1.53
1	1	4.0	4.0	10						1.0			1.0									B381298	117.35	118.87	0.018			VA05067824	1.52
5	6	0.1	0.5	57									0.1									B381299	118.87	120.40	0.113			VA05067824	1.53
2	1	2.0	2.5	60																		B381300	120.40	121.92	<0.005			VA05067824	1.52
3	1	1.0	2.0	40						1.0												B381301	121.92	123.44	<0.005			VA05067824	1.52
3	1	1.0	2.0	40						1.0												B381302	121.92	123.44	<0.005	DUP		VA05067824	1.52
	4			10	20																	B381303	123.44	124.97	<0.005		Veinlets	VA05067824	1.53
1	1	1.0	1.0	55							3.0											B381304	124.97	126.49	0.006			VA05067824	1.52
4	6	0.1	0.4	60		0.2	b	0					1.0									B381305	126.49	128.02	0.006		Aspy in selvage	VA05067824	1.53
2	6	0.1	0.2	60		0.2	b	0					0.1									B381306	128.02	128.64	<0.005		Aspy in selvage	VA05067824	0.62
0																						B381307	128.64	129.54	<0.005			VA05067824	0.90
1	1	5.0	5.0	50									0.1									B381308	129.54	130.86	<0.005			VA05067824	1.32

DRILL LOG LEGEND - P1	DATE:	PAGE 7 of 10	
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		130.86	131.82	QZZ. Light grey green, minor chl alt present giving green color. Py crystals on frac faces. Qtz, cb and sulphide veins crosscut.			2			
80		131.82	133.29	MSED. Grey brown. Py on frac faces. Soft, easy to scratch. Foliation @38-40°		2	2	1	1	
80		133.29	142.20	QZZ - Light grey. Residual foliation @134.11m -> 50°, @140.71m -> 35-45°. Increase in qtz/sulphide veins and sulphide concentrations. Core is broken and fractured until 141.03m where it regains competency. @134.61m - 4cm massive aspy vein @80° to CA @140.21m - 4cm massive sulphide vein @5° to CA; 40% sph, 20% py @140.39m - 8cm massive sulphide vein @50° to CA; 40% aspy, 30% sph, 20% py. Also present in the vein is a vug containing lead grey delicate acicular crystals. These are likely some form of Sb-Pb sulphide. Possibly stibnite, but more likely boulangerite or jamesonite. See photo. @134.61m marks the beginning of a zone of massive sulphide veining continuing until 158.40m. Veining may be related to the QZZ and very silicious MSED in the interval. Sulphides found throughout this core are more often found in QZZ than in MSED.		1	2			
80		142.20	144.31	Silicious MSED - Dark grey. Sulphides are almost absent in this interval. Foliation @142.20m -> 30-32°, @143.26m -> 37-40°						
80		144.31	144.63	APL dyke. Uphole contact @20° to CA. Downhole @35° to CA. Diss py and aspy present.						
80		144.63	146.30	QZZ - Light grey. No visible foliation. @145.46m - 7cm sulphide vein @55° to CA, 50% py, 10% aspy, 5% sph						
80		146.30	150.76	Silicious MSED - Dark grey, reduced veinage and sulphide content. Foliation @146.30m -> 45-47°, @147.83m -> 30-35°, @149.35m -> 45-47°		1	1	1	1	
80		150.76	151.48	QMON - Dark grey-green. 25% K-spar, 25% plag, 10% qtz, 15% bt. Uphole contact @80° to CA. Downhole contact not visible		1	3	1		
80		151.48	152.40	MSED - Dark grey. Foliation @20-25°. Silicious		1	1	1	1	
80		152.40	167.64	QZZ - Light grey to grey. There is an increase in sulphide veining. Foliation @152.40m -> 30-32°, @161.54m -> 32-35°. @154.67m - 60cm gouge @30° to CA @156.50m - 30cm grey qtz vein. No visible contact. 1% sulphides @156.80m - 2cm massive sulphide vein @60° to CA, 90% py, 10% aspy @158.15m - 15+ cm massive sulphide vein. Broken, with no visible contacts. Possibly 15-20cm or more in width. Sulphide concentrations range from 50% py & 50% aspy to 30% py & 70% aspy. The difference in concentrations could indicate more than one vein. Partial reconstruction yielded a contact angle near 75° @166.48m - 50cm gouge with QZZ fragments @45° to CA			1			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	5.0	5.0	50									0.1									B381309	129.54	130.86	0.005	PD/CA		VA05067824	1.32
																						B381310	STANDARD 1A		0.916	1A		VA05067824	
2	1	1.0	2.0	30						0.1												B381311	130.86	131.82	0.007			VA05067824	0.96
0																						B381312	131.82	132.59	0.008			VA05067824	0.77
0																						B381313	132.59	133.29	<0.005			VA05067824	0.70
0																						B381314	133.29	134.11	<0.005			VA05067824	0.82
0																						B381315	134.11	134.61	0.005			VA05067824	0.50
																						B381316	BLANK		<0.005			VA05067824	
1	6	4.0	4.0	80									40.0		20.0							B381317	134.61	134.71	0.18			VA05067824	0.10
2	6	0.2	0.2	50											10.0							B381318	134.71	135.64	0.011			VA05067824	0.93
2	1	0.2	0.4	20																		B381319	135.64	137.16	0.008			VA05067824	1.52
2	1	0.2	0.1	40																		B381320	137.16	138.68	0.013			VA05067824	1.52
2	6	0.1	0.2	55																		B381321	138.68	140.21	0.016			VA05067824	1.53
2	6	0.1	0.2	55																		B381322	138.68	140.21	0.016	DUP		VA05067824	1.53
1	6	4.0	4.0	5						20.0					40.0							B381323	140.21	140.39	0.177		Massive Sulphides	VA05067824	0.18
1	6	8.0	8.0	50						20.0			40.0		30.0		0.1					B381324	140.39	140.61	2.08		Massive Sulphides	VA05067824	0.22
1	1	3.0	3.0	60									0.1									B381325	140.61	141.73	0.007			VA05067824	1.12
2	1	2.0	4.0	40									0.1									B381326	141.73	142.20	0.015			VA05067824	0.47
0																						B381327	142.20	143.26	0.006			VA05067824	1.06
2	1	2.0	3.0	40							0.1											B381328	143.26	144.31	<0.005			VA05067824	1.05
2	1	2.0	3.0	40							0.1											B381329	143.26	144.31	<0.005	PD/CA		VA05067824	1.05
																						B381330	STANDARD 7G		4.51	7G		VA05067824	
0																						B381331	144.31	144.63	0.008			VA05067824	0.32
2	1	3.0	5.0	40						0.1			0.1									B381332	144.63	145.46	0.013			VA05067824	0.83
1	6	7.0	7.0	55						50.0			10.0		5.0							B381333	145.46	145.53	4.52		Massive sulphides	VA05067824	0.07
0																						B381334	145.53	146.30	0.014			VA05067824	0.77
1	3	0.5	0.5	50																		B381335	146.30	147.83	<0.005			VA05067824	1.53
																						B381336	BLANK		<0.005		Crosscuts foliation	VA05067824	
1	6	0.5	0.5	55						1.0			5.0		0.1							B381337	147.83	149.35	0.014		Veinlets/crosscuts foliation	VA05067824	1.52
	4	0.1		10	25																	B381338	149.35	150.76	<0.005			VA05067824	1.41
0																						B381339	150.76	151.48	0.015			VA05067824	0.72
1	4	0.2	0.2	30																		B381340	151.48	152.40	<0.005		Crosscuts foliation	VA05067824	0.92
0																						B381341	152.40	153.92	<0.005			VA05067824	1.52
0																						B381342	152.40	153.92	<0.005	DUP		VA05067824	1.52
1	1	2.0	2.0	30						0.1												B381343	153.92	154.67	0.019			VA05067824	0.75
0																						B381344	154.67	155.45	0.026		Gouge	VA05067824	0.78
3	6	0.1	0.3	45						1.0												B381345	155.45	156.50	0.019			VA05067824	1.05
1	1	30.0	30.0							1.0			1.0									B381346	156.50	156.80	0.027			VA05067824	0.30
1	6	2.0	2.0	60						90.0			10.0									B381347	156.80	156.87	5.69		Massive Sulphides	VA05067824	0.07

DRILL LOG LEGEND P1	DATE:	PAGE 9 of 10	
DRILL HOLE # : **DG05-296C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		167.64	172.21	MSED - Less silicious than most previous intervals. 80% of the veins are carbonate. Foliation @167.64m -> 32-35°, @169.16m -> 22-25°, @170.69m -> 32-33°, @168.63m, MSED is brecciated and cemented by cb, until 169.32m, where it contacts the MSED @40° to CA		2	2	2	1	
80		172.21	175.44	Silicious HFLS. Grey to dark grey with violet and green banding. Veining is nearly absent. Uphole contact with MSED @40° to CA. Foliation @172.21m -> 40-42°, @173.74m -> 45-50°		2	3	1	1	
80		175.44	187.90	QZZ and HFLS - Light grey with violet and green banding. 80% of interval is QZZ with intermittent bands of HFLS, the largest being 85cm @182.03m. Foliation is visible in HFLS @40-45° to CA. @172.6m - Cave. Pebbles include MSED and massive sulphides - no sample @185.80m - 3cm qtz/cb/sulphide vein @ 40° to CA. 60% aspy		2	2			
80		187.90	191.56	Silicious MSED + HFLS: Dark grey to black. Minor HFLS (5%) containing green and violet banding. Foliation @187.90m-> 45-50°, @188.98m -> 60-62°, @190.50m -> 60-62°		3	2	2	1	
80		191.56	192.60	QZZ - Light grey, no visible foliation. @192.40m - 3cm massive sulphide vein @40° to CA. 20% aspy, 20% py						
80		192.60	198.12	Silicious MSED - Light grey-green. More Chl than most intervals. Foliation @192.60m -> 45-47°, @193.55m -> 60-62°, @195.07m -> 40-42°, @196.60m -> 40-42° @197.92m - 1cm sphalerite vein @40° to CA @198.02m - 10cm QMON						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Jul 29-Aug 5

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
	1									0.1												B381348	156.87	158.15	0.056		Broken pieces	VA05067824	1.28
	1									0.1												B381349	156.87	158.15	0.057	PD/CA		VA05067824	1.28
																						B381350	STANDARD 6F		2.82	6F		VA05067824	
1	6	15.0	15.0	75						50.0			50.0									B381351	158.15	158.30	15.25		Massive Sulphides	VA05067824	0.15
3	6	0.2	0.4	65						15.0								40.0				B381352	158.30	160.02	0.226			VA05067824	1.72
2	6	0.1	0.2	30									1.0									B381353	160.02	161.54	0.084			VA05067824	1.52
2	3	1.0	1.5	50						0.1			0.1									B381354	161.54	163.07	0.03			VA05067824	1.53
0																						B381355	163.07	164.59	<0.005			VA05067824	1.52
																						B381356	BLANK		<0.005			VA05067824	
	1																					B381357	164.59	166.12	0.008		Broken pieces	VA05067824	1.53
	1																					B381358	166.12	167.64	0.248		Broken pieces	VA05067824	1.52
5	1	1.5	4.5	50									10.0									B381359	167.64	169.16	0.212			VA05067824	1.52
3	1	2.0	2.5	30							0.1											B381360	169.16	170.69	<0.005			VA05067824	1.53
1	4	1.0	1.0	150																							Crosscut foliation		
3	1	1.0	1.7	50																		B381361	170.69	172.21	0.009			VA05067824	1.52
																						B381362	170.69	172.21	0.01	DUP		VA05067824	1.52
1	1	1.5	1.5	60																		B381363	172.21	173.74	0.075			VA05067824	1.53
5	1	1.0	2.5	60																		B381364	173.74	175.44	<0.005			VA05067824	1.70
1	1	2.0	2.0	40																		B381365	175.44	176.78	0.015			VA05067824	1.34
	4			10	20																	B381366	176.78	178.31	0.083		veinlets	VA05067824	1.53
	4			10	20																	B381367	178.31	179.83	0.038		veinlets	VA05067824	1.52
4	1	1.0	3.5	58									1.0									B381368	179.83	181.36	0.021			VA05067824	1.53
4	1	1.0	3.5	58									1.0									B381369	179.83	181.36	0.022	PD/CA		VA05067824	1.53
																						B381370	STANDARD 4D		0.446	4D		VA05067824	
2	1	1.0	1.5	45																		B381371	181.36	182.88	0.042			VA05067824	1.52
2	1	2.0	3.0	30									0.1									B381372	182.88	184.40	0.024			VA05067824	1.52
1	6	3.0	3.0	40									60.0									B381373	184.40	184.80	3.47		Massive sulphides	VA05067824	0.40
2	1	2.0	3.0	30									0.1									B381374	184.80	185.93	0.035			VA05067824	1.13
	4			30	60																	B381375	185.93	187.45	0.028		veinlets	VA05067824	1.52
																						B381376	BLANK		<0.005			VA05067824	
0																						B381377	187.45	187.90	0.006			VA05067824	0.45
1	1	6.0	6.0	60																		B381378	187.90	188.98	0.162			VA05067824	1.08
3	4	0.5	0.7	20																		B381379	188.98	190.50	0.596			VA05067824	1.52
0																						B381380	190.50	191.56	0.306			VA05067824	1.06
3	6	0.1	0.3	45									1.0									B381381	191.56	192.40	0.013			VA05067824	0.84
3	6	0.1	0.3	45									1.0									B381382	191.56	192.40	0.009	DUP		VA05067824	0.84
1	6	3.0	3.0							2.0		3.0	10.0									B381383	192.40	192.60	1.345		Massive Sulphides	VA05067824	0.20
0																						B381384	192.60	193.55	<0.005			VA05067824	0.95
1	1	3.0	3.0	45									0.1									B381385	193.55	195.07	<0.005			VA05069644	1.52
1	4	1.5	1.5	25																		B381386	195.07	196.60	0.073			VA05069644	1.53
1	6	1.0	1.0	40											30.0							B381387	196.60	198.12	0.009			VA05069644	1.52
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-297C

PROJECT: Dublin Gulch - 1735

ELEVATION: 996 m

BEARING: 000 | DIP: -60°

DATE STARTED: 21-Jul-05 | DATE COMPLETED: 25-Jul-05

LOGGED BY: Melodie Stone & Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459608 NORTHING: 7099297

COORD SYSTEM: NAD 83: EASTING: 459489 NORTHING: 7099481

NAD 27 (CORRECTED for historic grid): EASTING: 459578 NORTHING: 7099307

SECTION LINE(historic grid): 459575 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 16.5m

Deviation:

Casing: 16.5m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B382618 - B382680

Requisition #: MASP448STRGOL.05Q Date Shipped: 5-Aug-05

Lab Record #: VA05066355 Date Received: 11-Aug-05

Sample Sequence: B382681 - B382700, B363201 - B363323

Requisition #: MASP448STRGOL.05Q Date Shipped: 8-Aug-05

Lab Record #: VA05067826 Date Received: 12-Aug-05

Duplicates:	382622; 382642; 382662; 382682; 383202; 383222; 383242; 383262; 383282; 383302; 383322
Preparation Duplicate/ Check Assay:	382629; 382649; 382669; 382689; 383209; 383229; 383249; 383269; 383289; 383309
Standards:	382630; 382650; 382670; 382690; 383210; 383230; 383250; 383270; 383290; 383310
Blanks:	382636; 382656; 382676; 382696; 383216; 383236; 383256; 383276; 383296; 383316

FROM	TO	LITHOLOGY
16.50	82.10	MSED
82.10	119.54	HFLS
119.54	161.00	GND
161.00	161.17	pebbles, variable lithologies
161.17	265.18	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	338.2	-61.6	004.2	005.2
134.11	342.0	-62.9	008.0	009.0
201.17	335.0	-48.3	001.0	002.0
265.18	335.0	-48.3	001.0	002.0
	SUSPECT SURVEYS			

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 1 of 14	
DRILL HOLE # : DG05-297C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-16.50	0.00	16.50	Casing - No recovery						
80	16.50-82.10	16.50	35.05	Highly oxidized to crumbly gravel and sand texture. Competent rocks with visible laminations are in chunks up to 10cm long. From 16.50 to 24.20m rock is dominated by yellowish brown clay to crumbly angular gravel. From 24.20 to 34.80m texture is course sand to angular cobbles and the colour is dark grey with dark brown limonite on all broken faces. There is a 25cm zone of yellowish brown from 34.80 to 35.05m. No qtzite or veins in section so no samples. Foliation is not visible over much of section; Where it is: @21.00m: 10°, @22.45m: 20° - 160° (folded), @24.80m: 20°, @28.60m: 30°, x-cutting qtz/carb veinlet at 120°, @31.90m: 5°, x-cutting carb vn to 120°, @33.00m: 10°.	4			2		
80		35.05	42.30	More competent but still heavily oxidized MSED. Aphanitic texture and mineralogically separated between mafic, felsic and pure qtz laminations. Foliation measurements: from 35.05-35.35m: 105-120°, @36.65m: 60°, @38.50m: 125°, @39.90m: 40-65°, and @42.10m: 40°. Speckled oxidation product of iron within qtz vns (up to 15%) could be hematite or old magnetite (1-2mm grains). "Vein" from 40.27-40.57m has saccharine texture; looks like qtizite but is deemed a vn as it has similar angles as nearby vns x-cutting foliation.	4			1	1	
80		42.30	51.05	MSED: Crumbly coarse sand (75%) to 10cm lengths of core (25%); MSED is zoned (~2m) to mafic-rich and felsic rich sections; All with fine foliation still visible; Qtz veins still crosscut foliation. Foliation: At 42.35m = 45°; @44.6m = 50°; @46.4m = 50°; @47.7m = 30°; @49.0m = 15°; @50.5m = 30° TCA.	3			2	1	
80		51.05	58.64	MSED: Mineralogically separated MSED into wide zones of laminated mafics and pure qtz approx 40cm wide on avg; 10cm yellow clay-rich zone at 57.2m; Gravel clay from 57.5-57.91m; Carb in irregular veinlets; Stained with limonite; Foliation: At 51.3m = 25° TCA; @52.25m = 30° TCA; @53.9m = 25° TCA; @55.6m = 50° TCA; @56.45m = 45° TCA; @58.0m = 30° TCA; Various indicators of extension and compression: at 51.72m a qtz bleb appears to be old vein compressed to interact with and re-route foliation in MSED, or could be compressed post-separation in MSED; other zones have feldspars concentrated at the edges of pure quartz as well. These are not considered veins here; "Veins" are typically associated with calcite-siderite (limonite) and have selvages.	2			2	2	
80		58.64	64.68	MSED: Predominant color is medium to light brown, from intense oxidation of iron-rich rock. Non-oxidized zones include more felsic minerals and quartz layers. Porphyroblastic texture stands out against laminated, oxidized sections. Porphyroblasts possibly andalusite (tabular aggregates). First appearance of hornfels at 60.50-60.70m. Foliations: @58.8m = 40° TCA; @60.60m = 55° TCA; @62.00m = 30-50° TCA; @63.4m = 50° TCA; @64.3m = 55° TCA.	4	1		2	2	
80		64.68	74.17	MSED: Oxidation, limonite staining and carbonate-infused clays are greatly reduced; Rock is Biot-Hornfelsed. Veins and irregular blebs of qtz with minor carbonate still appear, are generally roughly parallel to foliation or are within it, with augen texture. Some veins crosscut the foliation and are noted here. Between 65.53m - 67.06m no veins appear. Qtz blebs (>4cm in diameter) have offshoots of qtz parallel to and at a complementary angle (90° TCA) to foliation, eventually pinching out. Foliations: @ 64.68m = 50°; @66.0m = 50°; @67.2m = 50°; @68.45m = 45°; @70.0m = 50°; @71.0m = 45°; @72.6m = 45°; @73.85m = 45° TCA.	2	2		1	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	3	0.2	0.2	60		0.5	q	5	5													B382618	27.43	28.46	**0.024**			VA05066355	1.03
1	3	0.4	0.4	60		0.0																B382619	30.48	32.00	**0.006**			VA05066355	1.52
2	1	1.0	2.0	5		2.0	q	2	5	tr								5.0				B382620	35.05	36.58	**0.053**			VA05066355	1.53
3	1	6.0	13	50		0.0				tr								5.0				B382621	36.58	38.10	**0.148**			VA05066355	1.52
3	1	6.0	13	50		0.0				tr								5.0				B382622	36.58	38.10	**0.023**	DUP		VA05066355	1.52
3	1	1.5	3.5	30		0.5	q/cb	2	5	2.0								5.0				B382623	38.10	39.62	**0.010**		cuts strong foliation	VA05066355	1.52
3	1	1.5	3.0	45		0.0				10								4.0				B382624	39.62	40.27	**0.025**			VA05066355	0.65
1	1	30	30	20		0.0				4.0								5.0				B382625	40.27	40.57	**0.020**			VA05066355	0.30
0																						B382626	40.57	41.15	**0.031**		possibly selvage from large qtz vein	VA05066355	0.58
2	1	1.0	2.0	5		0.5	q/cb	2	5	5.0								4.0				B382627	41.15	42.30	**4.810**			VA05066355	1.15
2	1	1.0	1.3	130	150	1.0	q	2	4	5.0								5.0				B382628	42.30	43.21	**0.603**			VA05066355	0.91
2	1	1.0	1.3	130	150	1.0	q	2	4	5.0								5.0				B382629	42.30	43.21	**0.169**	PD/CA		VA05066355	0.91
																						B382630	STANDARD 2B		**3.040**	2B		VA05066355	
2	1	4.0	6.0	50		4.0	q	4	2	7.0								5.0				B382631	43.21	44.20	**0.014**			VA05066355	0.99
3	1	1.0	3.0	140		6.0	q	3	2	2.0								5.0				B382632	44.20	45.72	**<0.005**			VA05066355	1.52
3	1	1.0	2.5	140	160	2.0	q	4	3	5.0								5.0				B382633	45.72	47.24	**<0.005**			VA05066355	1.52
																							47.24	48.77					1.53
																							48.77	50.29					1.52
																							50.29	51.05					0.76
3	1	1.0	2.0	130	150	6.0	q	1	4	2.0			0.1					2.0					51.05	51.82					0.77
2	1	0.5	1.0	150		2.0	q/cb	2	4	0.1													51.82	53.34					1.52
1	6	0.5	0.5	130		1.0	q/k/cb	3	5	40.0	0.1							5.0				B382634	53.34	54.16	**<0.005**		ox'd hem 55%	VA05066355	0.82
1	[illegible]	50.0	50.0	100		0.0				2.0			0.1					5.0				B382635	54.16	54.86	**<0.005**			VA05066355	0.70
4	[illegible]	1.0	3.5	100	165	2.0	q/k/cb	3	4	0.1								5.0					54.86	56.39					1.53
1	1	1.5	1.5	0	140	20.0	cb/q/k	4	4	4.0								5.0					56.39	57.91			cb used same pathway		1.52
1	1	1.0	1.0	140		2.0			5	5.0								5.0					57.91	58.64			with hem		0.73
2	1	4.0	6.0	135	160	2.0	q/cb	2	5	0.1								5.0					58.64	59.44					0.80
2	1	2.0	3.0	130	150	1.0	q/cb	2	5	5.0			0.1					4.0					59.44	60.96					1.52
																						B382636	BLANK		**0.006**			VA05066355	
5	1	2.0	5.5	150	90	0.0				8.0			0.1					4.0				B382637	60.96	62.48	**0.190**		one small vein @ 90°	VA05066355	1.52
3	1	2.0	4.0	150	140	0.0				3.0								5.0				B382638	62.48	64.01	**0.486**			VA05066355	1.53
2	1	2.5	4.5	150	120					0.1			2.0					5.0					64.01	64.48					0.47
2	1	1.0	2.0	160	135	2.0			5								0.1						64.48	65.53			20° and 55° in one deformed vein. Other vein @ 20°		1.05

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 3 of 14	
DRILL HOLE # : DG05-297C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		74.17	79.85	MSED: With fine laminations and fat qtz blebs; From 74.17m to 75.83m color is light orange from intense carbonate and limonite throughout qtz-rich zone. Texture crumbly, with quartz pieces ~ 2cm in diameter. Foliations: @74.4m = 35°; @76.0m = 20°; @77.5m = 40°, @79.0m = 40° TCA.	3			1	1	
80		79.85	82.10	Very crumbly MSED covered with limonite to 80.77m, average size of 2cm; From 80.77m-81.70m, more competent but intensely stained yellow and orange (lim and carb); At 81.7-82.1m, competent with few limonite-covered fracture faces. Foliations: @ 80.1m = 50°, @81.9m = 50°, @82.1m = 45° TCA.	3				2	
81	82.10-119.54	82.10	88.39	MSED: Aphanitic HFLS with qtz veins highly rearranged and often parallel to foliation. Their appearance is compacted, rounded blebs, with 'tails' frequently pointing into foliation. HFLS color is dark purplish black. Foliation: @82.5m = 40°, @84.2m = 40°, @85.9m = 40°, @87.55m = 40°.	2				1	
81		88.39	92.96	MSED: HFLS continues; Silicified 'veins' parallel to foliation are less irregular-shaped, more smooth eyes within foliation. Veins crosscutting foliation contain sulphides and have jagged edges, incorporating into foliation. Real aspy associated with veins in this zone. Foliations: @88.6m = 40°, @90m = 60°, @91.5m = 60°, @92.8m = 60°.	2		1		1	
81		92.96	107.80	MSED: Silicified Hornfels, deep purple to greenish purple. Qtz veins (with carbonate) still parallel to and at a high angle to foliation, contain aspy/some scorodite, and moly. QZZ zones (v. silicifed) up to 20cm, wide contain disseminated aspy in tiny (1mm) grains, unaltered. HFLS sections show porphyroblasts of andalusite in random orientations acicular. Foliations: @ 93.5m = 60°; @94.8m = 55°, @96.1m = 40°; @97.6m = 50°; @99.4m = 40°; @101.0m = 40°; @102.2m = 40°; @103.6m = 55°; @104.6m = 35°; @107.0m = 40° TCA.	1				1	
81		107.80	113.53	(MSED) Silicified HFLS; Qtz-rich zone with very minor carbonate and limonite on fracture faces; From 111.25 - 113m is QZZ; Section is 80% qtz, 20% is 1-2mm veinlets of HFLS, biot, chl, ser, cb. These veinlets are derived from pieces of HFLS trapped into intruding qtz from the GND intrusion (just below 119.54m); Foliations: @107.9m = 30°; @109.65m = 40°; @110.90m = 30 - 50°; @112.22m = 35-50°.	1	1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

PAGE 4 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																							65.53	67.06					1.53
5	1	1.0	4.0	140		2.0	q	2	4	3.0							2.0	5.0				B392639	67.06	68.58	**0.018**			VA05066355	1.52
1	1	0.4	0.4	145		1.0	q	4	1													B392640	68.58	70.10	**0.005**			VA05066355	1.52
6	1	1.0	6.0	140	160	2.0			5	5.0							0.1	5.0				B392641	70.10	71.63	**0.008**			VA05066355	1.53
6	1	1.0	6.0	140	160	2.0			5	5.0							0.1	5.0				B392642	70.10	71.63	**0.008**	DUP		VA05066355	1.53
1	4	0.3	0.3	150		0.0				0.0													71.63	73.15					1.52
																							73.15	74.17					1.02
1	1	2.0	2.0	100																			74.17	75.83					1.66
2	1	5.0	9.0	140		0.0				0.1								5.0					75.83	76.85					1.02
2	1	1.0	2.0	140																			76.85	77.72					0.87
3	3	0.5	1.3	140	150	0.5	q/cb	2	4	1.0								5.0					77.72	79.25					1.53
3	1	10.0	20.0	50		0.0																							
2	1	1.0	1.2	140		0.5	q/cb	2	3														79.25	79.85					0.60
1	3	0.5	0.5	140		1.0	q/cb	3	1														79.85	80.77					0.92
1	1	3.0	3.0	80																			80.77	82.10					1.33
5	1	2.0	7.5	140	140	1.0	cb/q	2	3	0.1								5.0				B382643	82.10	83.34	**0.147**			VA05066355	1.24
4	1	4.0	8.0	130	15	2.0	cb/q	3		0.1			0.1					4.0	4.0			B382644	83.34	84.20	**0.014**		selvage appears perpendicular to foliation, but not parallel	VA05066355	0.86
3	1	15.0	32.0	50		4.0	q/cb	3	2				5.0						4.0			B382645	84.20	85.34	**0.040**			VA05066355	1.14
1	3	1.0	1.0	145		0.0				1.0								5.0											
2	1	3.0	6.0	140	30	8.0	q/cb	4	2	3.0								5.0				B382646	85.34	86.20	**0.006**			VA05066355	0.86
2	1	20.0	25.0	40		4.0	q/cb	2	2				5.0						4.0			B382647	86.20	86.87	**0.022**			VA05066355	0.67
3	1	6.0	9.0	150		6.0	q/cb	4	2	3.0												B382648	86.87	87.61	**0.066**			VA05066355	0.74
																						B382649	86.87	87.61	**0.065**	PD/CA		VA05066355	0.74
																						B382650	STANDARD 4D		**0.420**	4D		VA05066355	
4	1	3.0	10.0	125	45	1.0	q/cb	2	1													B382651	87.61	88.39	**0.044**			VA05066355	0.78
3	1	2.0	6.0	150		2.0	q/cb	1	3													B382652	88.39	89.92	**0.019**			VA05066355	1.53
4	3	3.0	5.0	50	35	1.0	q/cb	2		1.0								5.0											
4	1	4.0	7.0	40	125	3.0	q/cb	4	3				5.0						0.0			B382653	89.92	91.44	**0.238**			VA05066355	1.52
2	3	1.0	1.5	50		1.0	q/cb	3	1																				
4	1	1.0	4.0	60	120					2.0			2.0					5.0	5.0			B382654	91.44	92.96	**0.115**			VA05066355	1.52
4	3	0.5	1.8	155									15.0						0.0										
4	1	1.5	5.0	30	50	2.0	q/cb	3	3	0.1			10.0					2.0	3.0			B382655	92.96	94.49	**0.084**			VA05066355	1.53
																						B382656	BLANK		**<0.005**			VA05066355	
4	1	2.0	5.5	160	135	1.0	q/cb	3	1				5.0						2.0			B382657	94.49	96.01	**0.120**			VA05066355	1.52
4	1	2.0	8.0	150	45	2.0	q/cb	3	2				3.0				0.1					B382658	96.01	97.54	**0.011**			VA05066355	1.53
7	1	6.0	15.0	60	150	2.0	q/cb	1	3		3.0		2.0					1.0	5.0			B382659	97.54	99.06	**<0.005**		selvage on veins to 150°	VA05066355	1.52
5	1	1.0	4.0	60	140					1.0			2.0						5.0			B382660	99.06	100.58	**<0.005**			VA05066355	1.52
3	1	1.5	4.0	145		2.0	q/cb	1	1				1.0				1.0					B382661	100.58	102.11	**0.014**			VA05066355	1.53
3	1	1.5	4.0	145		2.0	q/cb	1	1				1.0				1.0					B382662	100.58	102.11	**0.005**	DUP		VA05066355	1.53
2	1	1.5	2.5	50	140	0.0				1.0								5.0				B382663	102.11	103.63	**<0.005**			VA05066355	1.52
6	1	20.0	30.0	40	130	1.0	q/cb	3	1													B382664	103.63	105.16	**<0.005**			VA05066355	1.53
10	1	8.0	25.0	40	160	1.0	q/p	4	1	1.0			4.0					5.0	0.0			B382665	105.16	106.68	**0.006**		p=pyroxene	VA05066355	1.52
2	1	0.4	0.7	135	35	0.0				1.0								5.0				B382666	106.68	107.80	**<0.005**			VA05066355	1.12
4	1	1.0	4.0	40																		B382667	107.80	108.90	**<0.005**		ox'd py, not po	VA05066355	1.10

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 5 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81		113.53	119.54	MSED: Last section of MSED's contact wi GND at 119.54m; HFLS more effected by carbonate, somewhat broken up, still 70% competent core or angular cobbles, 30% carb-clay and HFLS-Clay (dark purple, flaky to crumbly and soft).		1		1	2	
10	119.54-161.00	119.54	136.28	GND: As MSED/HFLS acted as a caprock to carbonate intrusion, calcite is concentrated in this uppermost section of GND. It is more permeable than HFLS as well. Carbonate seen in veinlets, veins and throughout GND matrix (btwn qtz, biot, plag, etc.), causing it to be crumbly and soft and carb-clay rich. Nothing competent until 126.49m where core lengths are up to 15cm. One length of 20cm at 134.92m. 22cm wide zone of dark grey clay at 129.4 - 129.62m contains ox'd py? All sericite/carbonate altered.						
10		136.28	143.26	GND: Section is 90% alt'd with carb and chlorite throughout the matrix of GND, such that the color is greenish-brown-grey. At 142.60m, a qtz/carb vein contains large spahlerite and chalcopyrite in up to 1cm irregular to subhedral bands. Oxidation noted is predominantly within sulphides-pyrite.	1	1	2		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL																				
										Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	0.5	3.0	150						3.0	2.0							5.0				B382668	108.90	109.73	0.009			VA05066355	0.83
																						B382669	108.90	109.73	0.009	PD/CA		VA05066355	0.83
6	1	1.5	4.5	15	35	1.0	q	4	0								5.0					B382670	STANDARD 5E		1.405	5E		VA05066355	
5	1	6.0	9.0	40		1.0	q	2	0								0.1					B382671	109.73	111.25	<0.005			VA05066355	1.52
2	3	0.5	1.0	150		0.0				0.0												B382672	111.25	112.22	0.039			VA05066355	0.97
3	3	0.5	1.5	150		0.0																B382673	112.22	112.78	<0.005			VA05066355	0.56
5	1	0.5	2.5	125		0.0					1.0		3.0						5.0		2.0	B382674	112.78	113.53	<0.005			VA05066355	0.75
3	1	5.0	8.0	153		2.0	chl/ser	3	1		2.0		5.0						5.0			B382675	113.53	114.60	<0.005		no aspy visible, only scor	VA05066355	1.07
																						B382676	BLANK		<0.005		branching veins, no selvage	VA05066355	
7	1	8.0	18.0	160	120	0.0							7.0						5.0			B382677	114.60	115.72	<0.005			VA05066355	1.12
4	1	2.0	6.0	140									5.0						4.0			B382678	115.72	116.02	<0.005			VA05066355	0.30
9	1	1.0	9.0	130		0.0					1.0								2.0			B382679	116.02	117.35	<0.005			VA05066355	1.33
4	3	2.0	3.0	40									3.0						0.0			B382680	117.35	118.87	<0.005			VA05066355	1.52
4	1	4.0	8.0	40	155	1.0	cb	1	0				0.1									B382681	118.87	119.54	0.006			VA05067826	0.67
4	1	4.0	8.0	40	155	1.0	cb	1	0				0.1									B382682	118.87	119.54	0.006	DUP		VA05067826	0.67
0																						B382683	119.54	120.40	0.094			VA05067826	0.86
2	3	1.0	2.0							0.1												B382684	120.40	121.92	0.295		pieces/ crumbly	VA05067826	1.52
2	1	6.0	7.0	50	40	14.0	q/cb/chl	3		5.0			5.0					5.0				B382685	121.92	123.44	13.450		clean' aspy, ox'd py in 1mm lenses	VA05067826	1.52
3	3	3.0	9.0	40	60	10.0	cb	4	0				0.1						5.0			B382686	123.44	124.97	0.119			VA05067826	1.53
3	3	4.0	7.5	35	130	10.0	cb/cbl	4		5.0								5.0				B382687	124.97	126.49	0.293			VA05067826	1.52
2	1	1.0	2.0	40	15	2.0	q/chl	3	0	2.0			0.1					4.0				B382688	126.49	128.02	0.709			VA05067826	1.53
3	4	0.5	1.5	75																									
2	1	1.0	2.0	40	15	2.0	q/chl	3	0	2.0			0.1					4.0				B382689	126.49	128.02	1.165	PD/CA		VA05067826	1.53
3	4	0.5	1.5	75																									
																						B382690	STANDARD 6F		1.110	6F		VA05067826	
4	1	1.5	4.0	60		2.0	q/cb	3	1	5.0								5.0				B382691	128.02	129.54	0.560			VA05067826	1.52
1	1	1.5	1.5	20		2.0	q/cb	2	0													B382692	129.54	131.06	0.048			VA05067826	1.52
3	1	1.0	3.0	85	135	0.0				0.1								5.0				B382693	131.06	132.59	0.852			VA05067826	1.53
3	1	0.5	1.5	145		0.5	q/cb	3			10.0							3.0				B382694	132.59	134.11	0.055			VA05067826	1.52
1	3	1.0	1.0	70		2.0	q/cb	2		1.0								5.0				B382695	134.11	134.91	0.117			VA05067826	0.80
																						B382696	BLANK		<0.005			VA05067826	
6	1	2.0	6.0	20	55	1.0	q/cb	3	0		6.0		1.0									B382697	134.91	136.28	0.891			VA05067826	1.37
3	1	5.0	9.0	20	50	10.0	q/cb/chl	4		10.0	4.0		2.0					1.0				B382698	136.28	137.16	0.325			VA05067826	0.88
1	3	0.4	0.4	30		2.0	q/cb	4		4.0								5.0											
2	1	3.0	6.0	30	10	6.0	q/cb/chl	4		10.0								2.0				B382699	137.16	138.00	0.540			VA05067826	0.84
5	6	1.0	3.5	40		10.0	q	2		70.0	10.0		10.0					2.0											
1	1	4.0	4.0	50		10.0	q/cb/chl	4		10.0			2.0		4.0			2.0				B382700	138.00	138.68	0.167		sulphides conc at margins	VA05067826	0.68
2	4	0.4	0.8	35		3.0	cb	2		20.0								4.0											
1	1	4.0	4.0	50		60.0	cb/chl	4		8.0	10.0		1.0					3.0				B363201	138.68	140.21	0.794		sulph vein w/in qtz vein selvage	VA05067826	1.53
1	6	0.5	0.5	35						80.0								3.0											
1	4	0.5	0.5	40		30.0	cb/chl	4		10.0						1.0		4.0											
1	1	4.0	4.0	50		60.0	cb/chl	4		8.0	10.0		1.0					3.0				B363202	138.68	140.21	0.574	DUP		VA05067826	1.53
1	6	0.5	0.5	35						80.0								3.0											
1	4	0.5	0.5	40		30.0	cb/chl	4		10.0						1.0		4.0											
4	4	0.3	1.2	40	30	20.0	cb/chl	4		5.0								5.0				B363203	140.21	141.73	0.058			VA05067826	1.52
2	6	0.2	0.4	20		20.0	q/cb	4		60.0								5.0											
2	1	1.5	2.5	35	60	80.0	cb/chl	4		15.0	2.0							1.0				B363204	141.73	142.55	0.444			VA05067826	0.82
3	1	2.0	4.5	4		20.0				10.0	5.0							2.0				B363205	142.55	143.26	3.600			VA05067826	0.71
1	3	0.5	1.5	5								8.0				15.0													

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 1 of 14	
DRILL HOLE # : DG05-297C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		143.26	148.88	GND: Moderate carbonate and chlorite alteration around veinlets of carbonate and few quartz veins; Generally unaltered GND: One 1cm zone of medium-grey clay at 143.46m; Carb-rich clay; Another 10cm wide at 146.17m		1	2	1	2	
10		148.88	150.88	GND: Unaltered; A few small quartz veins with very minor carbonate, pyrrhotite					1	
10		150.88	161.00	GND: Moderate carbonate intrusion into 80% unaltered GND: Zones of shear/re-arrangement/sulphide-clay						
-1	161.00-161.17	161.00	161.17	Random sub-rounded pebbles, lithology includes argillite, qtzite, granite and granodiorite; Max pebble size 4 cm in diameter.						
10	161.17-265.18	161.17	162.04	GND: Mostly unaltered; 6cm section of moderate sericite alteration; Short (~10cm) section of highly fractured GND with carbonate and sericite on fracture faces.		3			1	
10		162.04	163.07	GND: At 162.25 - 162.59m = Moderate chlorite alteration; At 162.59 - 163m = Moderate sericite alteration. Unaltered GND + chl altered at contact at ~30° TCA; Gradual contact with chlorite and sericite altered GND.		3	4			
10		163.07	164.59	GND: From 163.07 to 164.59m = Moderate to intense chlorite alteration; Gradual contact into unaltered GND; Multiple carbonate veins; Extremely fractured from 164.54 - 164.59m.			4			
10		164.59	166.12	GND: Mostly unaltered GND: Multiple <2mm oxidized sulphide veins; Disseminated pyrite on fractures with slickenlines.						
		166.12	167.64	GND: Compositionally unaltered; Pyrite smeared along slicken-slides						
		167.64	168.18	Appears brecciated with oxidized sulphide veining (?). Main zone contained by sharp oxidized sulphide veins at ~45° TCA; Only minor veining outside zone grading back into GND.	4				5	
10		168.18	175.10	GND: Unaltered; minor sulphides (mostly po and py); Slip faces at 60° TCA (Carbonate faces); Multiple carbonate, quartz and sulphide veinlets.						
10		175.10	175.26	GND: Highly fractured; Fracture faces have chl slickenlines with minor diss py; Po veinlets with quartz selvages parallel to fractures.						
10		175.26	181.36	GND: With very abundant carbonate veining; At 179 - 181m = Carbonate veining takes on pink color; At 176.78 - 177.05m = Altered carbonate fault gouge with ~ 4mm oxidized sulphide vein with quartz selvage (1cm) in center of gouge and parallel to contact (At 60° TCA); GND has a darker grey appearance; Many fracture faces have slickenlines in contact with minor pyrite smearing (Slickenlines are randomly oriented).			1		3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, co = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	Sulphides: pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	Oxidation: oxide	scordite	biotite	other		From	To					
3	1	1.0	3.0	40		3.0	q/chl	3	0		5.0	2.0						3.0				B363206	143.26	144.78	0.513		10% py in one vein only	VA05067826	1.52
2	3	3.0	5.0	30	20	2.0	cb/chl	4	0	10.0	7.0	5.0	1.0						4.0										
3	1	3.0	6.0	40	30	2.0	q/chl	2	0		5.0	7.0										B363207	144.78	146.30	0.112			VA05067826	1.52
1	3	3.0	3.0	25		4.0	q/cb	3	1	20.0	4.0		2.0																
1	1	1.0	1.0	25		10.0	cb/chl	4	0	5.0	0.1							4.0				B363208	146.30	147.83	0.030		silicified zone around carb veins (not selvage)	VA05067826	1.53
5	4	0.5	1.0	10	35	0.0																							
1	1	1.0	1.0	25		10.0	cb/chl	4	0	5.0	0.1							4.0				B363209	146.30	147.83	0.032	PD/CA		VA05067826	1.53
5	4	0.5	1.0	10	35	0.0																							
																						B363210	STANDARD 2B		2.690	2B		VA05067826	
4	1	3.0	7.0	30		2.0	q/chl	3	0		10.0		3.0									B363211	147.83	148.88	2.620			VA05067826	1.05
4	1	1.0	3.0	40		1.0	q/cb	2			0.1							1.0				B363212	148.88	150.35	0.090			VA05067826	1.47
0																						B363213	150.35	150.88	0.013			VA05067826	0.53
3	1	1.0	2.0	35		1.0	q	3	0		5.0											B363214	150.88	152.40	0.075			VA05067826	1.52
0																						B363215	152.40	153.92	0.012			VA05067826	1.52
																						B363216	BLANK		<0.005			VA05067826	
5	6	0.3	2.1	60						100.0								5.0				B363217	153.92	155.45	0.037		wispy	VA05067826	1.53
4	1	1.5	3.5	25	65	2.0	q	2		2.0	5.0		5.0						3.0			B363218	155.45	156.97	0.108			VA05067826	1.52
2	1	2.0	3.0			1.0	q	3			5.0											B363219	156.97	158.50	0.030			VA05067826	1.53
2	4	0.5	0.9	70		0.5	cb	3																					
3	4	0.2	0.6	70		1.0	cb	3														B363220	158.50	160.02	0.027			VA05067826	1.52
4	1	1.0	4.0	30		1.0	q	4			2.0		0.1									B363221	160.02	161.00	0.016			VA05067826	0.98
4	1	1.0	4.0	30		1.0	q	4			2.0		0.1									B363222	160.02	161.00	0.077	DUP		VA05067826	0.98
																							161.00	161.17					0.17
6	3	1.0	2.5	30	60	1.0	q/s/cb	1			1.0		0.1		0.1							B363223	161.17	162.04	0.042			VA05067826	0.87
4	1	1.0	2.0	30							5.0		0.1									B363224	162.04	163.07	0.024		po only in one vein	VA05067826	1.03
9	1	1.5	3.5	30	150	1.5	q/s/cb	5		2.0	2.0		0.1					1.0				B363225	163.07	164.59	0.076		ox'd py in qtz vein	VA05067826	1.52
9	5	1.0	5.0	30	45	2.5	s/q	4		0.1	1.0							1.0				B363226	164.59	166.12	0.200			VA05067826	1.53
2	4	0.2	0.4	30	10	0.5	cb	4	0	3.0	9.0							2.0				B363227	166.12	167.64	0.261			VA05067826	1.52
2	6	0.5	1.0	60			q/s/cb	4	3	3.0								4.0				B363228	167.64	168.18	0.891			VA05067826	0.54
																						B363229	167.64	168.18	0.992	PD/CA		VA05067826	0.54
																						B363230	STANDARD 5E		1.340	5E		VA05067826	
2	1	0.3	0.5	30						0.1	0.1							1.0				B363231	168.18	169.16	0.308			VA05067826	0.98
6	1	0.3	1.0	30		0.8	q	4		0.1	1.0							1.0				B363232	169.16	170.69	0.037			VA05067826	1.53
3	1	0.5	0.8	30						0.1	0.1	0.1										B363233	170.69	172.21	0.079			VA05067826	1.52
6	1	1.0	3.0	45	30	0.5	q	3	0	2.0	3.0	0.1	0.1									B363234	172.21	173.74	0.636			VA05067826	1.53
							chl																						
8	1	0.8	30.0	30	60	3.0	q	4	0	0.1	5.0	0.1						1.0				B363235	173.74	175.26	1.760			VA05067826	1.52
	4						chl	3																					
																						B363236	BLANK		0.005			VA05067826	
3	4	3.0	4.0	30	10																	B363237	175.26	176.07	0.016			VA05067826	0.81
6	4	0.6	2.0	60		0.5	cb	2	0	0.1	3.0	0.1	0.1									B363238	176.07	176.78	0.063			VA05067826	0.71
6	1	1.0	3.0	40	60	0.1	cb	3		0.1	0.1		1.0						2.0			B363239	176.78	178.31	0.076			VA05067826	1.53
	4																												
3	6	0.5	1.6	45						50.0								3.0				B363240	178.31	179.83	0.404			VA05067826	1.52
	1	1.0								2.0																			
	4	0.3									1.0																		
4	1	1.0	3.0	30		0.5	q			0.1	1.0											B363241	179.83	181.36	0.078			VA05067826	1.53
	4	0.3																											
4	1	1.0	3.0	30		0.5	q			0.1	1.0											B363242	179.83	181.36	0.076	DUP		VA05067826	1.53

DRILL LOG LEGEND - P1	DATE: July 20-26th, 2005	PAGE 9 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		181.36	183.33	GND: Extremely carbonate altered GND (fault gouge?); Locally in contact with less altered GND parallel to core axis; Sharp contact with dark green, softer GND (CHL altered) at ~30° TCA.					5	
10		183.33	198.12	GND: Near parallel to core axis between chlorite altered GND and intensive carbonate alt'd GND; Core changes between the two; Local intense clay and carbonate alteration; At 196.45m = 4 parallel quartz veins of chlorite and quartz with minor (~1%) pyrrhotite.			3		3	
10		198.12	206.27	GND: Mostly unaltered GND; Thin <2mm veins of carbonate still dominant but are less than previous; Two locations of intensely altered (carb) fault breccia (displaced veins within breccia) with sharp contacts between 40-60° TCA; Slickenline on 20° face at 60° TCA.						
10		206.70	219.00	GND: Predominantly unaltered GND; with local zones of slight chlorite alteration; Very minor carbonate veinlets (Except 1cm carb vein at 10°); Quartz veining is dominantly with chlorite or sericite (?) alteration; Slip faces have chlorite +/- carbonate; 10° face + 30° slickenlines; 30° face with 70° slickenlines; 45° with 80° slickenlines.			2			

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
	4	0.3																											
2	1	1.0	1.3	30																		B363243	181.36	181.91	**0.053**			VA05067826	0.55
	4	0.3		90																									
1	4	1.0	1.0	60																		B363244	181.91	183.33	**0.163**			VA05067826	1.42
2	1	2.0	3.0	60																		B363245	183.33	184.40	**0.221**			VA05067826	1.07
3	1	3.0	6.0	40						1.0	5.0	0.1						1.0				B363246	184.40	185.93	**0.156**			VA05067826	1.53
2	1	1.5	2.0	60		0.5	q	5			3.0							1.0				B363247	185.93	187.45	**0.067**			VA05067826	1.52
3	1	1.5	2.2	30		0.5	q	3			1.0											B363248	187.45	188.98	**0.024**			VA05067826	1.53
	4	0.3	0.3	90																									
3	1	1.5	2.2	30		0.5	q	3			1.0											B363249	187.45	188.98	**0.043**	PD/CA		VA05067826	1.53
	4	0.3	0.3	90																									
																						B363250	STANDARD 6F		**2.810**	6F		VA05067826	
3	1	1.0	2.5	30						0.1								1.0				B363251	188.98	190.50	**0.060**		aspy in only one vein	VA05067826	1.52
2	1	1.0	2.0	30	60					1.0	0.1	0.1						1.0				B363252	190.50	191.32	**0.067**			VA05067826	0.82
1	6	1.5	1.5	40						0.1								3.0				B363253	191.32	192.58	**0.058**			VA05067826	1.26
0																						B363254	192.58	193.23	**0.026**			VA05067826	0.65
1	3	0.3	..3	30		0.5	q	3		3.0	1.0							1.0				B363255	193.23	193.78	**0.022**			VA05067826	0.55
																						B363256	BLANK		**<0.005**			VA05067826	
5	1	1.5	5.5	30	45	0.4	q	3		0.1	1.0							1.0				B363257	193.78	195.07	**0.040**			VA05067826	1.29
	5																												
	3																												
6	1	1.0	4.0	30	150	0.4	q	4			1.0							1.0				B363258	195.07	196.60	**0.027**			VA05067826	1.53
	4																												
2	1	0.5	1.0	30																		B363259	196.60	198.12	**0.017**			VA05067826	1.52
	4																												
9	1	2.0	7.5	30	45	0.5	q	4	0	0.1	2.0							1.0				B363260	198.12	199.64	**0.063**			VA05067826	1.52
	1																												
	6																												
6	1	2.5	6.0	45	30	3.0	q	5			2.0		0.1					1.0				B363261	199.64	201.17	**0.065**			VA05067826	1.53
	6																												
	5																												
6	1	2.5	6.0	45	30	3.0	q	5			2.0		0.1					1.0				B363262	199.64	201.17	**0.283**	DUP		VA05067826	1.53
4	6	1.0	2.5	45		2.0	q	4			2.0							1.0				B363263	201.17	202.69	**0.032**			VA05067826	1.52
	1																												
	3																												
2	"	1.5	2.5	30	45																	B363264	202.69	204.22	**0.069**			VA05067826	1.53
3	"	1.0	2.5	30	45	0.5	q	4			2.0							1.0				B363265	204.22	205.08	**0.041**			VA05067826	0.86
	6																												
8	1	1.0	7.0	45	30	0.3	q	4			2.0		0.1					1.0				B363266	205.08	206.27	**0.097**			VA05067826	1.19
8	1	1.0	3.5	45	30	1.0	q	2			3.0		1.0					1.0				B363267	206.27	207.26	**0.092**			VA05067826	0.99
	6																												
	3																												
	5																												
6	1	1.0	4.0	30	45	0.5	q	3			3.0											B363268	207.26	208.79	**0.052**			VA05067826	1.53
6	1	1.0	4.0	30	45	0.5	q	3			3.0											B363269	207.26	208.79	**0.049**	PD/CA		VA05067826	1.53
																						B363270	STANDARD 6F		**2.800**	6F		VA05067826	
3	1	1.5	2.8	30	0	0.5	q	2			3.0							1.0				B363271	208.79	210.31	**1.580**			VA05067826	1.52
	4						chl																						
4	1	2.0	3.5	30		0.5	q	3			3.0		1.0					1.0				B363272	210.31	211.84	**1.130**			VA05067826	1.53
	6						chl																						
7	1	2.0	5.0	30		0.5	q	3			3.0		0.1					1.0				B363273	211.84	213.36	**0.057**			VA05067826	1.52
	5						chl																						
4	1	1.0	4.0	30							2.0											B363274	213.36	214.88	**0.087**			VA05067826	1.52
5	1	1.5	3.5	30		1.0	q	4			10.0	1.0						1.0				B363275	214.88	216.41	**0.163**			VA05067826	1.53
	6						chl																						

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 1 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		219.00	222.50	GND: Intensely altered GND (sericite); Core is stained green and softer than unaltered GND; Unaltered/Altered ctc runs near parallel to core in places; Contact is moderately gradual; Abundant disseminated blebs of very fine grained pyrite (20%) within 2-3cm of contact with unaltered GND.		3				
10		222.50	236.42	Core alternates between unaltered and sericite altered GND (unaltered GND is more abundant); Contact w/ GND is shallow (0-20°); Secondary altered GND contains disseminated blebs of very fine grained py near the contact; Minor local chlorite altered GND at 228.6 - 228.68m with 10% very fine grained blebs of pyrite; Between 235.15 - 235.87m area of sericite alteration with carbonate alteration as well; Within zone is a 0.5cm pyrite vein at 30° with slickenlines at 60° TCA.		2				
10		236.42	237.15	GND: Intensely altered GND (mostly carbonate alteration with more sericite alteration - greenish hue); Very soft - possibly fault breccia; Thick (1.5cm) quartz veins are cross cut.				2	3	
10		237.15	242.16	GND: Return to alternating unaltered GND and sericite altered GND; Pyrite veins (0.05 - 0.5cm) are common in sericite altered GND; Pyrite associated with carbonate veinlets and qtz veins and disseminated on and around slip faces; Slip faces have chlorite; 20° face with 80° slickenlines; 60° face with 90° slicks; Qtz vein offset (dextral) by carbonate filled fracture.		1				
10		242.16	248.94	GND: Intense sericite alteration with local carbonate alteration; Local intensive sulphide veining and fracturing; Abundant pyrite veining (some offset by carbonate filled fractures) at shallow angles (0-30° TCA); Chloritic slip faces at 5-30° with lines at 60-80°; Sulphide/carbonate vein offset (sinistral) by 5cm.		3			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B363276	BLANK		<0.005			VA05067826	
6	1	0.5	3.0	30	60	1.0	q	4			5.0											B363277	216.41	217.93	0.044			VA05067826	1.52
	6						chl																						
3	1	1.5	2.0	45		0.8	chl	3		1.0	2.0											B363278	217.93	219.00	0.154			VA05067826	1.07
6	1	3.0	6.5	30	45					1.0	5.0							1.0				B363279	219.00	220.40	0.081			VA05067826	1.40
	5																												
	6																												
3	1	1.0	2.0	30		0.2	chl	2		1.0	1.0							1.0				B363280	220.40	221.38	0.026			VA05067826	0.98
2	1	0.4	1.0	30						2.0	1.0											B363281	221.38	222.50	0.152			VA05067826	1.12
2	1	0.4	1.0	30						2.0	1.0											B363282	221.38	222.50	0.031	DUP		VA05067826	1.12
4	1	1.0	3.0	30	10	0.5	chl	3			1.0											B363283	222.50	224.03	0.033			VA05067826	1.53
	3																												
	4																												
2	1	1.0	1.5	30							2.0											B363284	224.03	225.46	0.028			VA05067826	1.43
2	1	2.0	3.0	30						0.1	2.0							1.0				B363285	225.46	227.08	0.135			VA05067826	1.62
																						Missing							
3	1	2.0	4.0	45	30					0.1	2.0											B363287	227.08	228.60	0.092			VA05067826	1.52
	5																												
3	1	2.0	4.0	45	30					0.1	2.0											B363288	228.60	230.12	0.128			VA05067826	1.52
																						B363289	228.60	230.12	0.185	PD/CA		VA05067826	1.52
																						B363290	STANDARD 2B		2.980	2B		VA05067826	
3	1	1.0	3.0	30							1.0											B363291	230.12	231.65	0.020			VA05067826	1.53
4	1	2.0	3.0	30							2.0											B363292	231.65	233.17	0.117			VA05067826	1.52
8	1	1.5	6.5	30		1.0	q	4		0.1	2.0											B363293	233.17	234.70	0.474			VA05067826	1.53
	6																												
3	1	0.6	1.5	30		1.0	q	4			1.0							1.0				B363294	234.70	235.15	0.253			VA05067826	0.45
5	1	1.0	4.0	30		1.0	q	4			1.0											B363295	235.15	236.42	0.155			VA05067826	1.27
	6																												
																						B363296	BLANK		<0.005			VA05067826	
2	1	1.5	2.5	45																		B363297	236.42	237.15	0.165			VA05067826	0.73
3	1	1.0	2.5	45							1.0											B363298	237.15	237.82	0.440			VA05067826	0.67
3	1	0.6	1.5	30	60					1.0	2.0							1.0				B363299	237.82	238.85	0.116			VA05067826	1.03
	6																												
3	1	1.0	2.5	45	30	0.5	q	3			1.0							1.0				B363300	238.85	240.33	0.137			VA05067826	1.48
3	1	0.5	1.0	60	30	1.0	q/cb	3			0.1							1.0				B363301	240.33	241.12	0.105			VA05067826	0.79
	3						s																						
3	1	0.5	1.0	60	30	1.0	q/cb	3			0.1							1.0				B363302	240.33	241.12	0.102	DUP		VA05067826	0.79
	3						s																						
3	1	0.5	1.0	45	30	0.5	q	3		1.0	1.0		1.0					1.0				B363303	241.12	242.16	0.059			VA05067826	1.04
	5						s																						
3	1	1.0	2.0	30		0.5	cb	4		4.0	1.0							5.0				B363304	242.16	243.55	0.058			VA05067826	1.39
	6																												
6	6	1.5	2.0	20						60.0								20.0				B363305	243.55	244.75	0.081			VA05067826	1.20
	1																												
3	4	0.5	1.5	30	60					1.0												B363306	244.75	246.33	0.077			VA05067826	1.58
	6																												
5	6	2.0	3.5	30	45					10.0	1.0							1.0				B363307	246.33	247.72	0.100			VA05067826	1.39
	3																												
2	1	1.0	1.5	45	30																	B363308	247.72	248.94	0.087			VA05067826	1.22
2	1	1.0	1.5	45	30																	B363309	247.72	248.94	0.081	PD/CA		VA05067826	1.22
																						B363310	STANDARD 5E		1.360	5E		VA05067826	

DRILL LOG LEGEND P1	DATE: July 20-26th, 2005	PAGE 13 of 14	
DRILL HOLE # : **DG05-297C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		248.94	256.18	GND: Mostly relatively unaltered GND with local (20cm) zones of sericite alteration; Disseminated pyrite found in sericite altered zones; From 256.5 - 259.45m = core very fractured; Sericite/Chlorite alteration selvages along fractures and with chlorite on faces.		1	1		1	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 20-26th, 2005

LOGGED BY: M. Stone/ K. Piepgrass

PAGE 19 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	1.0	2.0	30	45						2.0							1.0				B363311	248.94	249.94	**0.052**			VA05067826	1.00
3	1	1.0	1.5	30	45					2.0	1.0							1.0				B363312	249.94	251.46	**0.071**			VA05067826	1.52
	6																												
3	1	1.0	2.5	30							2.0							1.0				B363313	251.46	252.98	**0.076**			VA05067826	1.52
4	1	1.0	4.0	30	45					0.1	1.0							1.0				B363314	252.98	254.51	**0.100**			VA05067826	1.53
	4																												
2	1	1.0	15.0	30						1.0	1.0											B363315	254.51	256.03	**0.052**			VA05067826	1.52
																						B363316	BLANK		**0.006**			VA05067826	
1	1	0.5	0.5	30							1.0							1.0				B363317	256.03	257.56	**0.056**			VA05067826	1.53
																						B363318	257.56	259.08	**0.057**		Core to fractured	VA05067826	1.52
4	1	1.0	3.5	45							2.0							1.0				B363319	259.08	260.60	**0.119**			VA05067826	1.52
3	1	1.0	2.5	45							2.0							1.0				B363320	260.60	262.13	**0.745**			VA05067826	1.53
4	1	1.0	2.5	45		0.5	q	3			2.0							1.0				B363321	262.13	263.65	**0.149**			VA05067826	1.52
	6																												
4	1	1.0	2.5	45		0.5	q	3			2.0							1.0				B363322	262.13	263.65	**0.197**	DUP		VA05067826	1.52
4	1	1.0	2.5	45	30	2.0	5	3		2.0	1.0							1.0				B363323	263.65	265.18	**0.353**			VA05067826	1.53

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-298C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 891m

BEARING: 000 | DIP: -50°

DATES DRILLING: July 21 - 26, 2005 | DATES LOGGING: August 7 - 13, 2005

LOGGED BY: Terry Croteau

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459302 NORTHING: 7099379

COORD SYSTEM: NAD 83: EASTING: 459184 NORTHING: 7099563

NAD 27 (CORRECTED for historic grid): EASTING: 459272 NORTHING: 7099389

SECTION LINE(historic grid): 459275 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 0.00 - 8.23m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B381388 - B381480

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Aug-05

Lab Record #: VA05070460 Date Received: 22-Aug-05

Sample Sequence: B381481 - B381576

Requisition #: MASP448STRGOL.05Q Date Shipped: 19-Aug-05

Lab Record #: VA05072073 Date Received: 25-Aug-05

Duplicates:	381402; 381422; 381442; 381462; 381482; 381502; 381522; 381542; 381562
Preparation Duplicate/ Check Assay:	381389; 381409; 381429; 381449; 381469; 381489; 381509; 381529; 381549; 381569
Standards:	381390 (3C); 381410 (4D); 381430 (2B); 381450 (5E); 381470 (4D); 381490 (3C); 381510 (2B); 381530 (5E); 381550 (6F); 381570 (7G)
Blanks:	381396; 381416; 381436; 381456; 381476; 381496; 381516; 381536; 381556; 381576

FROM	TO	LITHOLOGY
8.23	72.25	MSED
72.25	72.82	GND
72.82	95.49	MSED
95.49	95.89	GND
95.89	208.39	MSED
208.39	209.41	GND
209.41	243.36	MSED
243.36	280.42	GND

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
76.20	343.4	-55.7	9.40	10.40
152.39	347.7	-55.8	13.70	14.70
213.35	349.2	-57.2	15.20	16.20
280.40	351.2	-57.2	17.20	18.20

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 1 of 12		
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 8.23	0.00	8.23	Casing - No Recovery						
80				MSED - Varied composition. Derived from pelitic to arenaceous rocks. May be silicious or phyllitic. Alteration is commonly sericitic, with minor chloritic and argillic present. Foliation is initially at a much lower angle to CA than previous holes.						
80	8.23 - 72.25	8.23	18.29	MSED - Dark grey. Limonite is pervasive and heavily stains fracture faces. Foliation is at low angles to CA. Foliation @ 8.23m -> 10-12°, @9.14m -> 10-15°, @10.67m -> 30-32°, @12.19m -> 40-45°, @13.72m -> 30-32°, @15.24m -> 20-25°, @16.76m -> 0-10°. Recovery is poor. Core is broken into gravel sized pieces (70%) and 5cm or larger (30%). @16.76m, 18cm APL dyke @10° to CA. Fabric appears gneissic and is parallel to CA.	3	2		1	1	
80		18.29	32.73	Silicious MSED - Dark grey to dark blue. Foliation continues to be between 10° and 45° to CA. Lim is less pervasive, but continues on the fracture faces. Foliation @18.29m ->15-20°, @19.81m -> 25-30°, @21.34m -> 25-30°, @22.86m -> 22-25°, @24.38m -> 20-22°, @25.91m -> 20-25°, @27.43m -> 30-35°, @28.96m -> too broken for measurement, @30.48m -> too broken for measurement, @32.00m -> 30-35° - folded. @20.72m - 5cm APL dyke @85° to CA.	2					
80		32.73	36.72	Intense clay alt'n throughout section. Core is soft but coherent. @36.85m - 15cm gouge containing MSED frags - possible hydrothermal alt'n.	2			4	2	
70		36.72	54.86	QZZ - Light grey to grey. Residual foliation @ higher angles to CA (55-60°). Qtz veins increase in number and size, up to 35cm. 95% of the veins are 1-3cm in width. There is also a corresponding increase in sulphides, though less intense. 70% of the sulphides are found on fracture faces and 75% of the aspy has been altered to Scorodite. @50.29m - 9cm grey qtz vein @ 60° to CA @51.82m - 8cm grey qtz vein @ 50° to CA @53.34m - 35cm grey qtz vein @ 40° to CA, 5% scor			2	2	1	
80		54.86	58.63	Silicified MSED - light grey to grey. Lighter coloured qtz ellipsoids are banded by darker coloured feldspar, bt and hbl, giving the core a gneissic appearance. The banding passes through the veins indicating it was a later process. Veining is similar in intensity to above interval.						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	4.0	4.0																			B381388	8.23	8.63	<0.005			VA05070460	0.40
																						B381389	8.23	8.63	0.005	PD/CA		VA05070460	0.40
																						B381390	STANDARD 3C		0.142	3C		VA05070460	
0																							8.63	9.14			Broken - Poor recovery		0.51
3	1	0.2	0.6	20	140																		9.14	10.67					1.53
0																							10.67	12.19			Broken - Poor recovery		1.52
0																							12.19	13.72			Broken - Poor recovery		1.53
0																							15.24	16.76			Broken - Poor recovery		1.52
0																							16.76	18.29			Broken - Poor recovery		1.53
0																							18.29	19.81			Broken - Poor recovery		1.52
0																							19.81	21.34			Broken - Poor recovery		1.53
1	1	0.2	0.2	30									3.0					95.0					21.34	22.86			Crosscuts Foliation		1.52
0																							22.86	24.38					1.52
0																							24.38	25.91					1.53
	1	0.2																					25.91	27.43			Pieces		1.52
0																							27.43	28.96			Broken - Poor recovery		1.53
0																							28.96	30.48			Broken - Poor recovery		1.52
0																							30.48	32.00			Broken - Poor recovery		1.52
0																							32.00	32.73			Broken - Poor recovery		0.73
0																							32.73	33.53			Intense alt - veins not visible		0.80
0																							33.53	35.00			Intense alt - veins not visible		1.47
0																							35.00	36.58			Intense alt - veins not visible		1.58
0																							36.58	36.72			Intense alt - veins not visible		0.14
																							36.72	38.10					1.38
																							38.10	39.62					1.52
																							39.62	41.15					1.53
	1	2.0											0.1									B381391	41.15	42.67	0.005		Broken pieces	VA05070460	1.52
1	1	3.0	3.0	50						1.0								25.0				B381392	42.67	44.20	<0.005		Broken pieces	VA05070460	1.53
1	1	2.0	2.0	40						1.0								65.0				B381393	44.20	45.72	0.005			VA05070460	1.52
2	1	1.0	2.0	40						1.0								50.0				B381394	45.72	47.24	<0.005			VA05070460	1.52
1	1	1.5	1.5	70																		B381395	47.24	48.77	0.005			VA05070460	1.53
																						B381396	BLANK		<0.005			VA05070460	
2	1	6.0	10.0	60									10.0					50.0	50.0			B381397	48.77	50.29	0.019			VA05070460	1.52
3	1	9.0	15.0	30									1.0					75.0				B381398	50.29	51.82	0.007			VA05070460	1.53
3	1	8.0	17.0	50																		B381399	51.82	53.34	0.005		No visible sulphides	VA05070460	1.52
2	1	35.0	45.0	40									5.0						90.0			B381400	53.34	54.09	0.005			VA05070460	0.75
11	1	2.0	4.0	40	85					0.1												B381401	54.09	54.86	<0.005			VA05070460	0.77
																						B381402	54.09	54.86	<0.005	DUP		VA05070460	0.77
4	1	1.0	3.0	50																		B381403	54.86	55.40	<0.005		Crosscuts Foliation	VA05070460	0.54

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 3 of 12	
DRILL HOLE # : DG05-298C	FeOx: 0 = Unoxidized, 5 = Intensely Ox'd; Ser, Chl, etc: 0 = Unaltered, 5 = Intensely Altered	Carbonate: 0 = No Effervescence, 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION: Comments:	ROCK (Alteration): Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
70		58.63	60.96	QZZ - Same as previous QZZ interval, with a max vein size of 9cm.						
80		60.96	66.85	Silicious MSED - Dark grey. Qtz veins continue intensity and large size. Foliation @60.96m -> 50-52°, @62.48m -> 45-47°, @64.01m -> 50-55°, @65.53m -> 55-60° @66.35m - 10cm gouge. Contains angular 1-5cm MSED frags. No contact angle visible.		1	1			
70		66.85	68.58	QZZ - Light grey. Veins decrease in number to 2, and in size to a max of 0.2cm. Relic foliation is @45-50° to CA			1			
80		68.58	71.02	MSED - Dark grey, 40% argillite. Chl alt'n is increased, while ser alt'n decreases. Foliation @68.58m -> 45-47°, @70.10m -> 45-47°. There is an increase in veining compared to previous interval. @69.77m - conjugate vein set. 2cm grey qtz @60° and 115° to CA. 2cm bt selvage		1	2			
		71.02	72.25	Silicious MSED - same as above with a higher silica content. Likely due to contact with GND dyke @ 72.25m		1	2			
12	72.25 - 72.82	72.25	72.82	GND dyke - 30% qtz, 20% plag, 15% bt. Contact @20° to CA. The first 17cm of GND is bleached and contains only 1% bt. Veins are small (<0.2 cm) containing trace sulphides.						
80	72.82 - 95.49	72.82	88.79	MSED - Silicious, grey to dark grey. Veining is similar to previous MSED interval with a max of 4cm. Sulphide veins are present with 95% ranging from 0.1-0.2 cm Sulphides have been replaced by bt. Bt selvages are also common among qtz veins. Qtz and sulphide veinlets crosscut foliation. Foliation @72.82m -> 55-57°, @73.15m -> 50-52°, @74.68m -> 45-47°, @76.20m -> 40-45°, @77.12m -> 45-47°, @79.25m -> 50-55°, @80.77m -> 50-52°, @82.30m -> 60-62°, @83.82m -> 60-62°, @85.34m -> 60-62°, @86.87m -> 50-52°		1	1	1	1	
70		88.79	93.52	QZZ - Veining is reduced as is the sulphide content. Cb fills fractures. @90.36m - 29cm GND dyke @50° to CA. GND is bleached with 1% mafics present. Light green color, minor chl present.			1			
80		93.52	95.49	Silicious MSED - Dark grey, no major veining. Foliation @93.52m -> 60-62°, @94.49m -> 65-67°. @95.49m - contact with GND dyke @40° to CA		3	1	1	1	
12	95.49 - 95.89	95.49	95.89	GND Dyke - Light blue-grey color. Phaneritic, 10% bt, which is less than most GND in other holes. No visible veins.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	7.0	15.0	50									3.0						90.0			B381404	55.40	56.39	<0.005			VA05070460	0.99
6	1	0.5	3.0	60	115	0.1	b	2	0				0.1									B381405	56.39	57.91	<0.005		Aspy in selvages	VA05070460	1.52
6	1	1.0	2.5	50									0.1									B381406	57.91	58.63	0.005			VA05070460	0.72
3	1	0.2	0.6	35									1.0									B381407	58.63	59.44	<0.005			VA05070460	0.81
4	1	0.2	0.8	50						1.0										95.0		B381408	59.44	60.96	<0.005			VA05070460	1.52
																						B381409	59.44	60.96	<0.005	PD/CA		VA05070460	1.52
																						B381410	STANDARD 4D		0.450	4D		VA05070460	
6	1	6.0	11.0	60	130								1.0						95.0			B381411	60.96	62.48	<0.005			VA05070460	1.52
10	1	0.5	5.0	50		0.1	k	1	0				0.1						50.0			B381412	62.48	64.01	<0.005			VA05070460	1.53
5	1	5.0	11.0	55									0.1						50.0			B381413	64.01	65.53	<0.005			VA05070460	1.52
2	1	1.0	2.0	60									0.1									B381414	65.53	66.85	<0.005			VA05070460	1.32
2	1	0.2	0.4	50																		B381415	66.85	68.58	0.005			VA05070460	1.73
																						B381416	BLANK		<0.005			VA05070460	
4	1	2.0	6.0	60	115	2.0	b	4	0				3.0						95.0			B381417	68.58	70.10	<0.005			VA05070460	1.52
4	1	0.1	0.4	40									0.1						95.0			B381418	70.10	71.02	<0.005		Crosscuts Foliation	VA05070460	0.92
	1																					B381419	71.02	72.25	<0.005		Broken Pieces	VA05070460	1.23
4	1	0.1	0.4	45		0.1	q/k	2	0				0.1									B381420	72.25	72.82	0.005			VA05070460	0.57
2	1	1.0	1.5	45						0.1												B381421	72.82	73.15	0.006		Crosscut Foliation	VA05070460	0.33
																						B381422	72.82	73.15	0.008	DUP	Crosscut Foliation	VA05070460	0.33
5	1	1.5	4.5	50									0.1									B381423	73.15	74.68	0.010		Crosscut Foliation	VA05070460	1.53
2	1	0.5	1.0	45									0.1									B381424	74.68	76.20	<0.005		Crosscut Foliation	VA05070460	1.52
5	1	1.0	2.4	37																		B381425	76.20	77.72	0.006		Crosscut Foliation	VA05070460	1.52
6	1	1.0	4.0	50									1.0							90.0		B381426	77.72	79.25	0.005		Crosscut Foliation	VA05070460	1.53
4	1	1.5	3.0	50						0.1			0.1						10.0	90.0		B381427	79.25	80.77	<0.005		Crosscut Foliation	VA05070460	1.52
6	1	0.5	1.5	40									0.1							90.0		B381428	80.77	82.30	<0.005		Crosscut Foliation	VA05070460	1.53
																						B381429	80.77	82.30	<0.005	PD/CA		VA05070460	1.53
																						B381430	STANDARD 2B		3.270	2B		VA05070460	
3	1	1.0	1.4	30	60					1.0												B381431	82.30	83.82	<0.005		Crosscut Foliation	VA05070460	1.52
5	1	0.2	1.0	30		0.1	b	4	0				0.1									B381432	83.82	85.34	<0.005			VA05070460	1.52
4	1	0.2	0.8	30									0.1									B381433	85.34	86.87	<0.005			VA05070460	1.53
0																						B381434	86.87	88.39	0.005			VA05070460	1.52
1	1	3.0	3.0	50																		B381435	88.39	88.79	<0.005			VA05070460	0.40
																						B381436	BLANK		<0.005			VA05070460	
0																						B381437	88.79	89.92	0.097			VA05070460	1.13
0																						B381438	89.92	90.36	<0.005			VA05070460	0.44
1	6	0.1	0.1	25		0.1	b	4	0				0.1							95.0		B381439	90.36	90.60	0.005			VA05070460	0.24
1	1	6.0	6.0	70									0.1						95.0			B381440	90.60	91.44	0.025			VA05070460	0.84
3	1	2.0	2.4	60									0.1						95.0			B381441	91.44	92.96	<0.005			VA05070460	1.52
																						B381442	91.44	92.96	0.005	DUP		VA05070460	1.52
1	1	4.0	4.0	55									0.1						95.0			B381443	92.96	93.52	0.010			VA05070460	0.56
0																							93.52	94.49					0.97
0																							94.49	95.49					1.00
0																						B381444	95.49	95.89	<0.005			VA05070460	0.40

DRILL HOLE # : DG05-298C

FeOx: 0 = Unoxidized; 5 = Intensely Ox'd
Ser, Chl, etc: 0 = Unaltered; 5 = Intensely Altered
Carbonate: 0 = No Effervescence; 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80	95.89 - 208.39	95.89	104.91	Silicious MSED - Less silicious than previous intervals. Foliation becomes higher angle to CA. There is an increase in veining and sulphide concentrations. Py can be found on frac faces. Foliation @95.89m -> 64-67°, @96.01m -> 65-67°, @97.54m -> 55-60°, @99.06m -> 60-62°, @100.58m -> 67-70°, @102.11m -> 70-75°, @103.63m -> 70-72°, @105.16m -> 85-87° @103.63m - MSEDS are brecciated and cemented by carbonate. Intense ser on frac faces.						
70		104.91	112.94	QZZ - Shear Zone - QZZ is intensely altered and deformed. Core is brecciated and half is reduced to sand size grains of qtz. Qtz veins are the last to be deformed and 90% still visible. Veining is increased as are sulphide concentrations, though most are oxidized						
80		112.94	119.71	MSED - Dark grey to black, easy to scratch. Ser on frac faces. Chl occurs in bands of 5-20cm and is associated with veins. Veining is reduced from previous interval. Foliation @112.94m -> 50-55°, @114.30m -> 50-55°, @115.82m -> 45-50°, @117.35m -> 55-60°, @118.87m -> 35-40° @115.58m - 22cm SZ @ 10° to CA.		1	1		1	
70		119.71	123.24	QZZ - Light grey, increase in veins, 90% of sulphides oxidized. Residual foliation @ 45-60°, crenulated. Cb veinlets present and on frac faces.			1		1	
93		123.24	127.13	SZ - Sheared MSED and QZZ. Core appears brecciated and highly fractured. Intense argillic alt'n follows breccia. Contact angles range from 10-30°. Chl and ser alt'n also intense, but less than argillic. Cb alt'n is greater than chl and ser, but less than arg. Qtz veins present but are fracture or reduced to pebble sized pieces. Sulphides have been heavily oxidized (90%)		2	2	4	3	
80		127.13	138.88	Silicious MSED - Grey to dark grey. Increase in qtz veining but few visible sulphides. Qtz veins between foliations. Foliation @127.13m -> 50-60°, @128.02m -> 80-85° folded, @129.54m -> 40-45°, @131.06m -> 45-50°, @132.59m -> 40-45°, @134.11m -> 20-50 "s" shaped fold, @135.64m -> 57-60°, @137.16m -> 57-60°. Intense ser on frac faces. @138.78m - 3cm apl dyke @ 55° to CA		3	1	1	2	
70		138.88	147.05	QZZ & MSED - 80% QZZ with intermittent bands of silicious MSED 5-30cm long. The foliation in the MSEDS is crenulated or folded into "s" patterns, making it difficult to measure. Veining is reduced in this section. Contacts between QZZ and MSED do not have a preferred orientation. 90% are undulatory and random. @144.72m, 16cm APL dyke @45° to CA. Foliation where measurable @ 50-60°		1	2		1	
80		147.05	159.32	MSED & QZZ - 80% silicious MSED with bands of QZZ ranging from 10 - 60 cm in width. Veining is similar to previous interval and sulphides are not visible. MSEDS show less folding, but it is still present. Foliation @147.05m -> 40-42°, @147.83m -> 47-50°, @149.35m -> 47-50°, @150.88m -> 50-55°, @152.40m -> 45°, @153.92m -> 47°, @155.45m -> 49°, @156.97m -> 46°, @158.50m -> 53°. @ 151.95m - 84cm GND dyke @ 60° to CA. GND is bleached, with 1% bt present. Ser and CHL alt'n dominant. Two 0.1cm sulphide veinlets present @ 40° and 70° to CA.		2	1		1	
70		159.32	163.84	QZZ - Light grey. Increase in number and size of qtz veins (max 10cm). Chl alt'n is increased, more intensity around veins. Relic foliation is at lower angles to CA. Foliation @ 32° to CA. @ 160.08m - 10cm qtz vein @ 32° to CA. Chl on frac faces. @ 160.92m - 37cm HFLS. Cb veins present after HFLS <0.5cm @ 10-30° to CA			2		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval					
										Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	1	0.1	0.2	10																		B381445	95.89	97.54	0.005			VA05070460	1.65
0																						B381446	97.54	98.25	<0.005			VA05070460	0.71
2	1	1.0	1.2	75									0.1						90.0			B381447	99.06	100.58	<0.005			VA05070460	1.52
2	1	2.0	2.5	65									0.1						90.0			B381448	100.58	102.11	0.007			VA05070460	1.53
																						B381449	100.58	102.11	0.008	PD/CA		VA05070460	1.53
																						B381450	STANDARD 5E		1.535	5E		VA05070460	
2	1	1.0	2.0	40																		B381451	104.91	105.16	0.005			VA05070460	0.25
5	1	2.0	7.0	40									0.1					70.0				B381452	105.16	106.68	<0.005			VA05070460	1.52
4	1	3.0	8.0	30	60								0.1									B381453	106.68	108.20	0.013			VA05070460	1.52
1	1	1.0	1.0	30																		B381454	108.20	109.73	0.008			VA05070460	1.53
3	1	2.0	5.0	35									0.1									B381455	109.73	111.25	<0.005			VA05070460	1.52
																						B381456	BLANK		<0.005			VA05070460	
3	1	1.0	3.0	40									0.1					95.0				B381457	111.25	112.94	0.015			VA05070460	1.69
	1	2.0											1.0						90.0			B381458	115.12	116.52	<0.005			VA05070460	1.40
1	1	9.0	9.0	45									10.0						90.0			B381459	116.52	117.35	0.007			VA05070460	0.83
4	1	6.0	10.0	40									0.1						90.0			B381460	117.35	118.87	<0.005			VA05070460	1.52
2	1	4.0	9.0	40									0.1						90.0			B381461	118.87	119.71	0.006			VA05070460	0.84
																						B381462	118.87	119.71	<0.005	DUP		VA05070460	0.84
2	1	2.0	2.5	35																		B381463	119.71	120.40	<0.005			VA05070460	0.69
6	1	6.0	12.0	37									0.1									B381464	120.40	121.92	<0.005			VA05070460	1.52
4	1	2.0	3.0	75	40					0.1			0.1						75.0			B381465	121.92	123.24	<0.005			VA05070460	1.32
4	1	8.0	8.0	60									1.0						90.0			B381466	123.24	124.70	0.006		Sheared and broken	VA05070460	1.46
	1																					B381467	124.97	126.49	<0.005			VA05070460	1.52
	1																					B381468	126.49	127.13	<0.005			VA05070460	0.64
																						B381469	126.49	127.13	<0.005	PD/CA		VA05070460	0.64
																						B381470	STANDARD 4D		0.434	4D		VA05070460	
4	1	7.0	23.0	70									5.0						90.0			B381471	128.02	128.72	0.007			VA05070460	0.70
1	1	27.0	27.0	70									10.0						90.0			B381472	128.82	129.10	<0.005			VA05070460	0.28
3	1	2.0	5.0	60						0.1			0.1					25.0	90.0			B381473	129.59	131.06	<0.005			VA05070460	1.47
5	1	4.0	9.0	65						0.1			0.1					25.0	90.0			B381474	131.06	132.59	<0.005			VA05070460	1.53
5	1	3.0	8.0	60						0.1			0.1					25.0	90.0			B381475	132.59	134.11	<0.005			VA05070460	1.52
																						B381476	BLANK		<0.005			VA05070460	
4	1	2.5	5.0	80						0.1			0.1					25.0	90.0			B381477	134.11	135.22	<0.005			VA05070460	1.11
3	1	2.0	2.8	40									0.1						90.0			B381478	139.10	140.43	<0.005			VA05070460	1.33
2	1	9.0	11.0	70									0.1						90.0			B381479	149.35	149.65	<0.005			VA05070460	0.30
2	6	0.1	0.2	40	70								0.1							95.0		B381480	151.95	152.79	0.011			VA05070460	0.84
1	1	2.0	2.0	50																		B381481	159.32	160.02	0.006		No Visible Sulphides	VA05072073	0.70

DRILL LOG LEGEND - P1	DATE: August 7 - 13, 2005	PAGE 7 of 12	
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
80		163.84	169.93	MSED interbedded with QZZ and HFLS - Foliation is initially at a higher angle to CA, but several small intrusions cause lower angles and folding. The small intrusive bodies (1-2cm) @ 165.50m and 166.32m are aplite. HFLS can be found surrounding them. Foliation @163.84m > 43°, @164.49m -> 45°, @166.12m -> 25°, @167.64m - not measureable, @169.16m -> not measurable. @165.50m - foliation @10°,40°, and 10° in "S" fold (see drawing ~)		2	2		2	
70		169.93	172.21	QZZ - Light grey-green, chl alt'n dominant. Few qtz veins, cb veins more common. Residual foliation @ 50° to CA, becoming 35° at end of interval		1	2			
80		172.21	176.41	MSED - Soft, easily scratchable. Foliation @ 35° increasing to 50° @ 174.74m @174.52m - 62cm GND dyke. Bleached and sericitized, 1% bt. Uphole contact not visible, downhole contact @ 80° to CA.		1	2		1	
12		176.41	178.01	GND dyke - Bleached, 5% bt, grey green color. Chl higher than ser alt'n, minor cb alt'n. Fractures @40° and 140°. Four 2cm qtz veins present, with trace aspy. Downhole contact @45° to CA.		2	3		3	
						2	3		3	
81		178.01	185.93	HFLS - Violet, green, white. Cb veining increased. Foliation still visible. Foliation @178.01m -> 37°, @178.31m -> 50°, @179.83m -> 45°, @181.36m -> 50°, @182.88m -> 50°, @184.40m -> 45°. Cb veins are at low angles, 10-25°. Very few veins in interval. No samples.						
81		185.93	190.76	HFLS & QZZ - Same as previous interval with an increase in QZZ and veining. Core contains 30% QZZ. Foliation @ 185.93m -> 40°, @187.45m -> 37°, @188.93m->45°, @190.50m -> too broken. Cb veining is reduced to 1 - 2 cm vein @ 25° to CA						
81		190.76	195.07	HFLS - Dark blue, with violet and green. There is a larger increase in veining with a max of 75cm. The sulphides also increase, but they are oxidized 50-90%. Scor and bt are common oxidation types.						
81		195.07	208.39	HFLS - Argillic alt'n becomes dominant form, chl also major alt'n. Cb alt'n increased. Qtz veining shows a large decrease in size (Max 3cm) and in number. Po, cpy and aspy found in veins. Foliation difficult to measure due to shearing. Gouge is also common: @ 195.95m - 15cm clay with qtz eyes and frags. @ 198.36m - 7cm clay with qtz eyes, MSED frags @ 204.84m - 0.5cm wide, 34 cm long gouge @12° to CA - slip plane @ 205.74m - 10cm gouge @30° to CA. Clay with MSED frags and ser Alteration becomes more intense after 207.47m where 70% of core shows argillic alt'n. Diss py, aspy, found throughout		2	3	3	2	
12	208.39 - 209.41	208.39	209.41	GND dyke - Light grey, 5% bt. Ser alt on frac faces. No visible qtz veins or structures as core is broken. Minor cb veinlets (2). Uphole contact not visible, downhole @70° to CA.		1			1	
81	209.41 - 243.36	209.41	215.82	Silicious HFLS - Grey, violet, green, dark blue. Hard, silicious, increased qtz content as veins and qtz eyes. Diss po found throughout. Minor potassic alt'n. Chl, ser on frac faces. Foliation @209.41m -> 30°, @210.31m -> 30°, @211.84m -> 40°, @213.36m -> 45°, @214.88m -> 45°		2	2		1	1

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval					
						Selvages				Sulphides								Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
																						B381482	159.32	160.02	0.009	DUP	No Visible Sulphides	VA05072073	0.70
1	1	10.0	10.0	32																		B381483	160.02	160.40	<0.005		No Visible Sulphides	VA05072073	0.38
4	1	2.0	7.0	45																		B381484	160.40	160.92	<0.005			VA05072073	0.52
3	1	2.0	6.0	47						1.0												B381485	161.54	163.07	0.005			VA05072073	1.53
1	1	0.2	0.2	60																		B381486	174.46	175.18	0.015			VA05072073	0.72
2	1	0.2	0.4	50									0.1									B381487	176.41	176.78	0.036			VA05072073	0.37
2	1	0.2	0.4	50									0.1									B381488	176.78	178.01	0.028			VA05072073	1.23
																						B381489	176.78	178.01	0.036	PD/CA		VA05072073	1.23
																						B381490	STANDARD 3C		0.091	3C		VA05072073	
2	1	2.0	4.0	40						0.1												B381491	185.93	187.45	0.007			VA05072073	1.52
4	1	2.0	5.0	50						0.1												B381492	187.45	188.98	<0.005			VA05072073	1.53
3	1	1.0	1.4	55						1.0			0.1									B381493	188.98	190.50	0.033			VA05072073	1.52
0										0.1			0.1									B381494	190.76	192.02	<0.005		Diss sulphides	VA05072073	1.26
2	1	15.0	25.0	65									1.0						90.0			B381495	192.02	192.56	<0.005			VA05072073	0.54
																						B381496	BLANK		<0.005			VA05072073	
2	1	75.0	95.0							1.0			1.0									B381497	192.56	193.55	<0.005			VA05072073	0.99
3	1	9.0	20.0										0.1									B381498	193.55	195.07	0.037			VA05072073	1.52
3	1	1.0	2.5	50						0.1			0.1									B381499	195.07	196.60	0.007		Diss sulphides	VA05072073	1.53
3	1	2.0	4.0	30						1.0												B381500	196.60	198.12	0.005		Py in vein and diss	VA05072073	1.52
5	1	1.5	6.0	35						0.1								75.0				B381501	198.12	199.64	<0.005			VA05072073	1.52
																						B381502	198.12	199.64	<0.005	DUP		VA05072073	1.52
1	1	0.2	0.2	30						1.0			1.0									B381503	199.64	201.17	0.005		Diss sulphides	VA05072073	1.53
5	1	0.2	1.0	27									0.1					75.0				B381504	201.17	202.69	0.010		Crosscuts foliation	VA05072073	1.52
1	1	2.0	2.0	60									5.0						90.0			B381505	202.69	204.22	0.011			VA05072073	1.53
4	1	1.0	2.5	30							3.0							90.0				B381506	204.22	205.74	<0.005		Crosscuts foliation	VA05072073	1.52
2	1	3.0	4.0	30							3.0	1.0	1.0									B381507	205.74	207.26	0.005		Crosscuts foliation	VA05072073	1.52
1	1	1.5	1.5	60									0.1						90.0			B381508	207.26	208.39	<0.005			VA05072073	1.13
																						B381509	207.26	208.39	<0.005	PD/CA		VA05072073	1.13
																						B381510	STANDARD 2B		2.970	2B		VA05072073	
2	4	0.1	0.1	30																		B381511	208.39	209.41	0.008		Veinlets	VA05072073	1.02
1	1	0.5	0.5	40									1.0						90.0			B381512	209.41	210.31	<0.005			VA05072073	0.90
2	1	0.5	1.0	50							0.1		0.1						90.0			B381513	210.31	211.84	<0.005			VA05072073	1.53
7	1	6.0	20.0	40	140	2.0	Chl	4	0		1.0											B381514	211.84	213.36	<0.005		Po is diss and in selvage	VA05072073	1.52
5	1	2.0	6.0	50		0.5	chl	4	0		0.1											B381515	213.36	214.88	<0.005		Po is diss and in vein	VA05072073	1.52
																						B381516	BLANK		<0.005			VA05072073	
2	1	2.0	3.0	50		0.5	chl	4	0		0.1											B381517	214.88	215.82	0.026		Crosscuts foliation, po in veins and diss	VA05072073	0.94

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005	PAGE 9 of 12	
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
61		215.82	231.65	HFLS - Dark blue-grey to black. Poikiloblastic texture common. Core contains 10-15% bt, 10% andalusite -> biotite-andalusite HFLS. Cb present on 90% of frac faces. Cb also dominant form of veins (60%). Qtz veining increased from previous interval, as well there is a corresponding increase in sulphides. Residual foliation is crenulated and crosscut by the veins. Qtz veins follow foliation. @227.08m - 40 cm GND dyke. 15% bt, no qtz veins, cb veins present. Uphole contact @35°, downhole contact @40° to CA		2	3	1	3	
81		231.65	237.74	HFLS - Intensely altered. Ser on frac faces. Cb is pervasive and on frac faces. Foliation @231.65m -> 50°, @233.17m -> 25°, @234.70m -> 25°, @236.22m -> 27° @231.89m, 7cm gouge, clay rich with HFLS frags		2	1	2	3	
81		237.74	240.79	Silicious HFLS - Pervasive Cb is increased. Core is highly fractured. Alteration obscures most foliation. @239.27m - Core becomes powdery on surface, argillic alt'n increased with ser and chl. Transitional before GND		2	1	2	4	
81		240.79	243.36	Gouge - Core is white, and intensely altered to clay. Crumbles when touched. Fragments in gouge are QZZ. Transition zone between HFLS and GND. Residual foliation @242.32m -> 55° to CA. Cb is pervasive. No visible veins		2	2	4	4	
10	243.36 - 280.42	243.36	245.36	GND - 30% qtz, 35% plag, 15% bt, 15% kspar, 5% hbl. Core is initially bleached, cb pervasive, only 5% mafics. By 243.84m is 90% unaltered. @ 243.84m - recovery poor (19%), core is broken into rounded gravel sized pieces.		2		3	4	
10		245.36	257.56	GND - 70% unaltered GND. Cb in veinlets and pervasive. Chl can be found on frac faces. Small (<0.5 cm) sheeted vein sets make their first appearance, as do aspy veinlets. There is an increase in aspy and po in the veins, compared to previous intervals. Fractures are @45° (parallel to veining) and 145° (crosscut veining).			1		2	
10		257.56	271.27	GND - Same as previous interval, but contains less pervasive cb. The larger veins (>2cm) occur in areas of chloritic alt'n, which has also increased on fracture faces. @262.88m - Slickensides on 40° frac faces @80° from CA			2		1	

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	2.0	2.0	45							5.0	0.1	0.1									B381518	215.82	216.40	0.025		Large euhedral aspy (.3 cm)	VA05072073	0.58
4	1	0.5	2.0	50							3.0	0.1	1.0						90.0			B381519	216.40	217.93	0.088			VA05072073	1.53
4	1	5.0	14.0	35							1.0		1.0						50.0			B381520	217.93	219.46	0.018			VA05072073	1.53
3	4	1.0	1.4	120																									
6	1	6.0	13.0	50							0.1		5.0						90.0			B381521	219.46	220.98	<0.005			VA05072073	1.52
																						B381522	219.46	220.98	<0.005	DUP		VA05072073	1.52
2	1	1.0	2.0	60							0.1		0.1									B381523	220.98	222.50	0.009			VA05072073	1.52
10	4	0.2	2.0	120																									
1	1	1.0	1.0	60									0.1									B381524	222.50	224.03	0.030			VA05072073	1.53
8	4	0.5	1.9	120																									
3	1	2.0	3.0	35									0.1						90.0			B381525	224.03	225.55	0.042			VA05072073	1.52
5	4	1.0	4.0	35																		B381526	225.55	227.08	0.017			VA05072073	1.53
3	1	2.0	4.0	25						1.0								50.0				B381527	227.08	228.60	0.020			VA05072073	1.52
5	4	0.5	1.3	120																									
4	4	4.5	8.0	30						1.0			0.1					50.0				B381528	228.60	230.12	0.009			VA05072073	1.52
																						B381529	228.60	230.12	0.014	PD/CA		VA05072073	1.52
																						B381530	STANDARD 5E		1.440	5E		VA05072073	
1	3	1.0	1.0	50									0.1					50.0				B381531	230.12	231.65	0.005			VA05072073	1.53
9	4	0.2	1.8	130	170																								
2	1	0.2	0.4	50									0.1									B381532	231.65	233.17	<0.005			VA05072073	1.52
3	1	0.2	0.6	55									0.1									B381533	233.17	234.70	0.017			VA05072073	1.53
3	1	0.2	0.6	50																		B381534	234.70	236.22	0.012			VA05072073	1.52
5	1	0.2	1.0	55									0.1									B381535	236.22	237.74	<0.005			VA05072073	1.52
																						B381536	BLANK		<0.005			VA05072073	
7	1	0.2	1.4	50	85								0.1									B381537	237.74	239.27	0.008			VA05072073	1.53
2	1	0.2	0.4	55									0.1									B381538	239.27	240.79	0.010			VA05072073	1.52
0																						B381539	240.79	242.32	0.051			VA05072073	1.53
0																						B381540	242.32	243.36	0.033			VA05072073	1.04
0																						B381541	243.36	243.84	0.216			VA05072073	0.48
																						B381542	243.36	243.84	0.036	DUP		VA05072073	0.48
	1									0.1												B381543	243.84	245.36	0.012			VA05072073	1.52
4	1	3.0	3.6	35	45					1.0			3.0									B381544	245.36	246.89	0.043			VA05072073	1.53
4	1	2.0	3.9	45	70	0.2	k	3	0		1.0		5.0									B381545	246.89	248.41	0.114			VA05072073	1.52
8	1	0.5	2.2	45		0.2	q	3	0	0.1			10.0									B381546	248.41	249.98	0.094			VA05072073	1.57
3	1	1.0	1.4	45		0.2	q	3	0		0.1											B381547	249.98	251.46	0.061			VA05072073	1.48
3	1	1.0	1.4	45						1.0	0.1		5.0									B381548	251.46	252.98	0.085			VA05072073	1.52
																						B381549	251.46	252.98	0.095	PD/CA		VA05072073	1.52
																						B381550	STANDARD 6F		2.850	6F		VA05072073	
2	1	0.2	0.4	45							0.1	0.1	1.0									B381551	252.98	254.51	0.080			VA05072073	1.53
0																						B381552	254.51	256.03	0.033			VA05072073	1.52
4	1	0.2	0.8	45	10						3.0		1.0									B381553	256.03	257.56	0.087		More po present in low angle veins	VA05072073	1.53
2	1	2.0	4.0	45									0.1									B381554	257.56	259.08	0.098			VA05072073	1.52
6	1	3.0	5.2	57		4.0	chl	3	0	1.0			3.0									B381555	259.08	260.60	0.048		Aspy in vein and selvage	VA05072073	1.52
																						B381556	BLANK		<0.005			VA05072073	
5	1	2.4	2.4	50		5.0	chl	3	0		1.0	0.1	3.0									B381557	260.60	262.13	0.032		Aspy in vein and selvage	VA05072073	1.53
2	1	1.5	1.7	47									1.0									B381558	262.13	263.65	0.066			VA05072073	1.52

DRILL LOG LEGEND P1	DATE: August 7 - 13, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-298C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
11		271.27	275.84	GND - Finer grain size compared to previous interval. Increase in pervasive cb. Contains 25-30% mafics. There is a decrease in the number of qtz veins over this interval, but similar sulphide content. Fractures occur @30° and 40° to CA.			1		2	
10		275.84	278.89	GND - return to med grain-size. 70% of core shows chl alt'n. Veins increase in number, size and sulphide content. @277.37m - Core shows hydrothermal alt'n - clay with GND frags and qtz pebbles. Contact @ 20° to CA. @278.24m - 10cm grey qtz vein @35° to CA. Contains 3% aspy		1	3	2	1	
10		278.89	280.42	GND - Becomes coarse grained, 20% of core shows chl alt'n. @278.89m - 15cm grey qtz vein @ 60° to CA. 3% aspy @280.16m - core is 10% diss po.			2			
	EOH									

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 7 - 13, 2005

LOGGED BY: Terry Croteau

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages				Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	6	0.1	0.1	50									70.0																
7	1	0.2	1.4	40							3.0											B381559	263.65	265.18	0.024			VA05072073	1.53
6	1	2.0	3.8	30	20	2.0	chl	3	0				5.0									B381560	265.18	266.70	0.253			VA05072073	1.52
3	1	0.2	0.6	35									20.0									B381561	266.70	268.22	0.261			VA05072073	1.52
																						B381562	266.70	268.22	0.309	DUP		VA05072073	1.52
5	1	1.5	3.9	42									30.0									B381563	268.22	269.75	0.184			VA05072073	1.53
3	1	1.0	1.2	50									5.0									B381575	269.75	271.27	0.065		Missed Sample	VA05072073	1.52
1	1	1.0	1.0	35									10.0									B381564	271.27	272.80	0.156			VA05072073	1.53
2	1	0.2	0.2	40									5.0						50.0			B381565	272.80	274.32	0.057			VA05072073	1.52
5	1	2.0	4.5	35							1.0											B381566	274.32	275.84	0.015			VA05072073	1.52
5	1	1.0	3.2	25																		B381567	275.84	277.37	0.289			VA05072073	1.53
0																						B381568	277.37	278.24	0.334		Not visible due to alt	VA05072073	0.87
																						B381569	277.37	278.24	4.460	PD/CA		VA05072073	0.87
																						B381570	STANDARD 7G		13.900	7G		VA05072073	
1	1	10.0	10.0	35									3.0									B381571	278.24	278.34	1.050			VA05072073	0.10
0																						B381572	278.34	278.89	6.900		Not visible due to alt	VA05072073	0.55
1	1	15.0	15.0	60									3.0									B381573	278.89	278.94	0.029			VA05072073	0.05
2	1	0.2	0.4	35							10.0		1.0									B381574	278.94	280.42	0.079		Po is diss	VA05072073	1.48
																						B381576	BLANK		0.137			VA05072073	
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-299C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION:

BEARING: 000 | DIP: -50°

DATE STARTED: 26-Jul-05 | DATE COMPLETED: 30-Jul-05

LOGGED BY: Kevin Piepgrass (Aug 7 - 14, 2005)

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459658 NORTHING: 7099319

COORD SYSTEM: NAD 83: EASTING: 459539 NORTHING: 7099505

NAD 27 (CORRECTED for historic grid): EASTING: 459628 NORTHING: 7099329

SECTION LINE(historic grid): 459628 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden: 3.35m

Deviation:

Casing: 3.35m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B363324 - B363423

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Aug-05

Lab Record #: VA05070531 Date Received: 23-Aug-05

Sample Sequence: B363424 - B363552

Requisition #: MASP448STRGOL.05Q Date Shipped: 14-Aug-05

Lab Record #: VA05070461 Date Received: 22-Aug-05

Duplicates:	363342; 363362; 363382; 363402; 363422; 363442; 363462; 363482; 363502; 363522; 363542
Preparation Duplicate/ Check Assay:	363329; 363349; 363369; 363389; 363409; 363429; 363449; 363469; 363489; 363509; 363529; 363549
Standards:	363330 (3C); 363350 (4D); 363370 (1A); 363390 (6F); 363410 (4D); 363430 (5E); 363450 (2B); 363470 (3C); 363490 (5E); 363510 (4D); 363530 (3C); 363550 (1A)
Blanks:	B363337, B363356, B363376, B363396, B363416, B363436, B363456, B363476, B363496, B363516, B363536

FROM	TO	LITHOLOGY
3.35	67.06	MSED
67.06	294.13	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	AZ (+27 Corr)
201.2	340.5	-58.1	006.5	007.5
294.1	340.9	-57.7	006.9	007.9

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: July 26th to 30th, 2005	PAGE 1 of 12		
DRILL HOLE # : **DG05-299C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-3.35	0.00	3.35	Casing, No core						
80	3.35-21.67	3.35	10.67	Silicified sed (quartzite). Moderate qtz vning with few vns x-cutting. Core appears to have a pinkish colour to it (possibly k-spar alt'n?).	3					
80		10.67	21.67	Much of core is highly fractured with limonite on fractured surfaces. Coherent core is darker with near parallel qtz vning and foliation between 60° and 45° to CA. Core that appears darker is less oxidized. Qtz vn selvages have pinkish colour possibly due to k-spar alt'n.	3					
80	21.67-67.06			Most of core has been intensely alt'd to clay with remnant qtz eyes or vn's. There are few intervals of dark fol'd core (as above). The clay alt'd core tends to be more ox'd (limonite) than dark MSED.	3			4		
80		39.00	41.00	Dark fol'd MSED. Fol'n gradually changes (down hole) from 1-30°. Fresher qtz vn's x-cutting fol'n at 70° to CA. Qtz vn's still ox'd but contain fresh f.g. py (1-2%). White laths (plag?) present along fol'n planes.	2					
80		41.00	44.20	Clay-rich broken core with short (20cm) intervals of dark fol'd MSED.	4			4		
80		44.20	44.83	Dark MSED with fol'n from 0 to 30°.	2					
80		45.70	46.80	Incoherent clay-rich core (fault gouge?)						
80		52.48	52.92	Dark MSED with fol'n about 30°.	2					
80		60.96	67.06	Broken up Quartzite. Size of blocks vary from mm-scale to 10cm in length.	2			1		
10	67.06-81.40	67.06	72.17	Highly frac'd GND with limonite on all frac faces. Frac'd blocks are coherent. Locally alt'd to clay (5cm flt gg?). Ox'd frac faces tend to be filled with carb.	2			1		
10		72.17	81.40	GND is intensely alt'd and frac'd with lim on faces. GND is incompetent (crumbly). Abundant carb frac filling. At 77.62m slip face at 60° with lines at 70° to CA.	3			3	2	
10	81.40-83.40	81.40	83.40	Grey GND, mod frac'd with limonite on frac faces. Multiple mm-scale limonitic frac's (~45°). Gradually fades into ser/chl alt and carb alt. Five near parallel vn's (carb, qtz and cb/q) within 30cm with ser alt'n in middle and chl alt'n surrounding. Slip face at edge of chl alt'n: 60° face with 60° lines.		3			3	
10	83.40-114.30	83.40	114.30	Back into grey GND. High % vning - mostly qtz with some carb. Qtz vns have small selvages. Possible VG mixed in with po and cpy. Thin cb vnlts tend to have wide ser selvages overprinting some qtz vns. Local areas of greater frac'ing with carb alt'n/frac filling (10-50cm). At 88.79m: a 5cm clay alt'n (flt gg?). Slip faces: at 99.36m: face at 60° and lines at 70°, at 114.00m: face at 30° and lines at 50°.		1				

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS											% of VEIN & DISSEMINATED MATERIAL																					
							Selvages				Sulphides									Oxidation						Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	1.0	1.0	30														2.0				B363324	3.35	4.57	0.009			VA05070531	1.22
3	1	1.0	2.5	30	60					1.0								2.0				B363325	4.57	6.10	<0.005			VA05070531	1.53
3	1	0.4	1.0	10	45	0.2	q	5										30.0				B363326	6.10	7.62	<0.005			VA05070531	1.52
6	1	1.0	2.0	45	30	0.2	q	4		1.0								20.0				B363327	7.62	9.14	0.011			VA05070531	1.52
4	1	1.0	2.0	30														2.0				B363328	9.14	10.67	0.012			VA05070531	1.53
	6																														
4	1	1.0	2.0	30														2.0				B363329	9.14	10.67	0.009	PD/CA		VA05070531	1.53
																						B363330	STANDARD 3C		0.081	3C		VA05070531	
0																						B363331	10.67	12.19	0.019			VA05070531	1.52
0																						B363332	12.19	13.72	0.008			VA05070531	1.53
2	1	3.0	4.0	10		0.5	q	3	1									10.0				B363333	13.72	15.24	0.053			VA05070531	1.52
3	1	1.0	2.5	70														20.0				B363334	15.24	16.76	0.006			VA05070531	1.52
5	1	2.0	6.0	60	30													10.0				B363335	16.76	18.29	<0.005			VA05070531	1.53
																						B363336	BLANK		<0.005			VA05070531	
3	1	4.0	7.0	45														5.0				B363337	18.29	19.81	<0.005			VA05070531	1.52
0																							19.81	21.67					1.86
0																							21.67	36.14					14.47
3	1	2.0	3.0	45														5.0				B363338	36.14	36.58	<0.005			VA05070531	0.44
0																							36.58	39.00					
6	1	1.5	5.0	45	70					2.0								5.0				B363339	39.00	40.51	0.27			VA05070531	1.51
3	1	4.0	4.5	70	30													5.0				B363340	40.51	41.93	0.006			VA05070531	1.42
0																							41.93	44.20					2.27
0																							44.20	60.96					16.76
0																													
0																													
0																						B363341	60.96	62.48	<0.005			VA05070531	1.52
0																						B363342	60.96	62.48	<0.005	DUP		VA05070531	1.52
																						B363343	62.48	64.01	0.034			VA05070531	1.53
																						B363344	64.01	65.53	<0.005			VA05070531	1.52
0																						B363345	65.53	67.06	0.006			VA05070531	1.53
0																													
2	1	1.0	1.5	30	45	0.5	q	4	3									4.0				B363346	67.06	68.58	0.033			VA05070531	1.52
0																						B363347	68.58	70.10	0.037			VA05070531	1.52
3	1	1.0	2.0	45		0.5	q/chl	4	3	0.1			0.1					5.0	1.0			B363348	70.10	71.63	0.089			VA05070531	1.53
3	1	1.0	2.0	45		0.5	q/chl	4	3	0.1			0.1					5.0	1.0			B363349	70.10	71.63	0.069	PD/CA		VA05070531	1.53
																						B363350	STANDARD 4D		0.43	4D		VA05070531	
0																						B363351	71.63	73.15	0.061			VA05070531	1.52
0																						B363352	73.15	74.68	0.26			VA05070531	1.53
0																						B363353	74.68	76.20	0.087			VA05070531	1.52
0																						B363354	76.20	77.72	0.042			VA05070531	1.52
0																						B363355	77.72	79.25	0.063			VA05070531	1.53
																						B363356	BLANK		<0.005			VA05070531	
1	1	0.5	0.5	45		2.5	s/cb	4	4		1.0							3.0				B363357	79.25	80.77	0.066			VA05070531	1.52
0																						B363358	80.77	81.40	0.026			VA05070531	0.63
1	1	0.5	0.5	30						1.0												B363359	81.40	82.00	0.026			VA05070531	0.60
3	4	2.0	3.5	30	45						1.0		1.0					20.0	5.0			B363360	82.00	83.40	0.438			VA05070531	1.40
1	1	1.0	1.0	30									1.0					5.0	1.0										
3	3	0.2	0.6	10		0.5	cb/s	5	4		1.0							80.0											
9	1	1.5	5.0	30	45	0.5	Q	4			2.0	0.1	1.0					1.0	2.0			B363361	83.40	85.34	0.084			VA05070531	1.94
4	4	0.3	0.7	30	45	3.0	s/cb	4	2									90.0											
9	1	1.5	5.0	30	45	0.5	Q	4			2.0	0.1	1.0					1.0	2.0			B363362	83.40	85.34	0.145	DUP		VA05070531	1.94
4	4	0.3	0.7	30	45	3.0	s/cb	4	2									90.0											
3	1	0.4	1.0	10	45	0.2	q	4	1				2.0					1.0	1.0			B363363	85.34	86.87	0.058			VA05070531	1.53

DRILL LOG LEGEND - P1	DATE: July 26th to 30th, 2005	PAGE 3 of 12	
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		95.64	97.16	Sample B363372 - heavily frac'd core and limonite. Remnant qtz vn's with euhedral aspy up to 0.4 x 0.2mm. Also, abundant cb frac's.	1					
10	114.30-120.40	114.30	120.40	Similar grey GND but with multiple zones of intense ser alt. Zones up to 75cm long (ser alt'n more intense in middle of zone commonly with limonite selvage among fractures). Fractures: at 119.60m - face at 70° and lines at 70°, at 119.80m - face at 40° and lines at 50°, at 117.76m - face at 10° and lines at 10°, at 114.40m - face at 10° and lines at 10°, at 114.41m - face at 60° and lines at 45°, and at 114.70m - face at 70° and lines at 80°. Carb frac filling still present but less abundant than above. Contact between GND and ser alt'n is distinct. Qtz vn'ing is slightly less abundant than above. Alt'n most likely due to fracturing.		5				
10	120.40-130.06	120.40	130.06	Back into grey GND (similar to 83.40-114.30m). Limonite and carb frac filling are becoming less prominent. Frac faces/slip faces are of limonite, carb or chl. Slickenlines are fairly abundant: at 124.57m-face at 45° lines at 45°, at 126.49m-face at 30°, lines at 60°, at 127.50m-face at 50°, lines at 50°, at 128.02m-face at 30° lines at 10°, at 129.34m-face @10° lines at 30°, and at 129.34m-face 30° w/ lines at 45°. Majority of qtz vn'ing is near parallel except at 129.84m where vn's are x-cutting.					1	
10	130.06-132.45	130.06	132.45	GND is much lighter in colour and softer and is carb-rich. Very minor qtz vn'ing. Sharp contact with grey GND. At 130.80m slip face at 10° with lines at 10° to CA.					3	
10	132.45-137.70	132.45	137.70	Grey GND with minor qtz vn'ing and minimal alt. Slip faces occur at 132.87m on 20° face w/ lines at 20°, at 133.72m on 70° face with 80° lines, and at 135.92m on 45° face and 45° lines						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2006

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
10	1	1.0	6.5	30	45	4.0	chl	4			3.0	0.1	1.0									B363364	86.87	88.39	0.418			VA05070531	1.52
5	1	1.0	4.0	30	45	0.2	q	5			2.0	0.1	0.1					0.1	0.1			B363365	88.39	89.92	0.406			VA05070531	1.53
3	4	0.5	1.0	45	30	6.0	s/chl	5										90.0											
2	1	1.0	2.0	45							0.1							0.1	0.1			B363366	89.92	90.66	0.023			VA05070531	0.74
0																						B363367	90.66	92.00	0.048		Broken Core	VA05070531	1.34
5	1	1.0	4.0	30	60	1.0	q/s	5	1		1.0	0.1	0.1					1.0				B363368	92.00	92.96	0.06			VA05070531	0.96
5	1	1.0	4.0	30	60	1.0	q/s	5	1		1.0	0.1	0.1					1.0				B363369	92.00	92.96	0.042	PD/CA		VA05070531	0.96
																						B363370	STANDARD 1A		0.829	1A		VA05070531	
6	1	1.0	2.5	45	10						1.0		0.1					1.0	0.1			B363371	92.96	94.49	0.093			VA05070531	1.53
7	1	1.0	3.0	10	60						1.0								1.0			B363372	94.49	95.64	0.099			VA05070531	1.15
0																						B363373	95.64	97.16	0.297		broken core	VA05070531	1.52
5	1	1.0	4.0	60	45						1.0							1.0	2.0			B363374	97.16	98.34	0.047			VA05070531	1.18
2	1	0.5	1.0	30						0.1	1.0							1.0				B363375	98.34	99.76	0.047			VA05070531	1.42
																						B363376	BLANK		<0.005			VA05070531	
4	1	0.5	2.0	30	45						5.0		0.1					1.0	1.0			B363377	99.76	100.58	0.051			VA05070531	0.82
0																						B363378	100.58	101.58	0.065		broken core	VA05070531	1.00
6	1	1.0	3.0	45	30						1.0							1.0	2.0			B363379	101.58	102.86	0.054			VA05070531	1.28
2	1	1.0	1.5	45							0.1							1.0	1.0			B363380	102.86	104.56	0.059			VA05070531	1.70
8	1	1.0	4.0	30	45	0.4	q/s	3			2.0	1.0	0.1					1.0	1.0			B363381	104.56	105.81	0.281			VA05070531	1.25
8	1	1.0	4.0	30	45	0.4	q/s	3			2.0	1.0	0.1					1.0	1.0			B363382	104.56	105.81	0.605	DUP		VA05070531	1.25
2	1	1.0	1.8	30	45						0.1											B363383	105.81	107.16	0.033			VA05070531	1.35
2	4	0.3	0.5	30	45	1.0	q	5	2									90.0											
2	1	3.0	4.0	45		0.3	q	5										1.0				B363384	107.16	108.20	0.038			VA05070531	1.04
0																						B363385	108.20	109.73	0.026		broken core	VA05070531	1.53
2	1	4.0	5.0	30							1.0							1.0				B363386	109.73	111.25	0.06			VA05070531	1.52
5	1	2.0	4.0	30		0.3	Q	5			1.0		2.0					1.0	1.0			B363387	111.25	112.78	0.068			VA05070531	1.53
6	1	2.0	6.0	30							2.0	0.1	1.0					1.0				B363388	112.78	114.30	0.191			VA05070531	1.52
2	6	0.5	0.7	1	90	0.5	q	3	2		50.0	2.0	2.0					20.0											
6	1	2.0	6.0	30							2.0	0.1	1.0					1.0				B363389	112.78	114.30	0.181	PD/CA		VA05070531	1.52
2	6	0.5	0.7	1	90	0.5	q	3	2		50.0	2.0	2.0					20.0											
																						B363390	STANDARD 6F		2.76	6F		VA05070531	
1	1	1.0	1.0	10							1.0							3.0	1.0			B363391	114.30	115.82	0.057			VA05070531	1.52
1	1	0.3	0.3	30		1.0	q	3		0.1	3.0		1.0					1.0	1.0			B363392	115.82	117.10	0.008			VA05070531	1.28
1	1	2.0	2.0	5							2.0		1.0					1.0				B363393	117.10	117.76	0.479			VA05070531	0.66
5	1	2.0	6.0	30	1	0.5	s	3	1		4.0	1.0						1.0	2.0			B363394	117.76	118.87	0.086			VA05070531	1.11
0																						B363395	118.87	120.40	0.071		Intense Alteration	VA05070531	1.53
																						B363396	BLANK		<0.005			VA05070531	
2	1	1.5	2.5	45							3.0	1.0										B363397	120.40	121.92	0.014			VA05070531	1.52
3	1	2.0	4.0	30							3.0	0.1							1.0			B363398	121.92	123.44	0.17			VA05070531	1.52
5	1	1.5	3.0	30							2.0		1.0						1.0			B363399	123.44	124.97	0.399			VA05070531	1.53
1	1	1.0	1.0	45							0.1								0.1			B363400	124.97	126.49	0.02			VA05070531	1.52
5	1	1.0	4.0	40	30					0.1	2.0	1.0	0.1									B363401	126.49	128.02	0.232			VA05070531	1.53
1	6	0.4	0.4	30		0.5	q	4		1.0	80.0	5.0	1.0																
5	1	1.0	4.0	40	30					0.1	2.0	1.0	0.1									B363402	126.49	128.02	0.059	DUP		VA05070531	1.53
1	6	0.4	0.4	30		0.5	q	4		1.0	80.0	5.0	1.0																
3	1	1.0	2.0	30	45	0.5	q/s	5			5.0	1.0	1.0									B363403	128.02	129.54	0.035			VA05070531	1.52
2	6	0.3	0.5	45		0.5	q	5			30.0	5.0	50.0																
4	1	4.0	8.0	40	130	0.5	q/s	5			1.0		0.1									B363404	129.54	130.06	0.028			VA05070531	0.52
1	1	0.5	0.5	60																		B363405	130.06	131.06	0.018			VA05070531	1.00
3	1	0.5	1.5	45	60	0.5	s	3			1.0								1.0			B363406	131.06	132.45	0.029			VA05070531	1.39
3	1	5.0	6.0	45	2						1.0											B363407	132.45	134.11	0.02			VA05070531	1.66
5	1	0.5	2.0	45							2.0								1.0			B363408	134.11	135.64	0.024			VA05070531	1.53
5	1	0.5	2.0	45							2.0								1.0			B363409	134.11	135.64	0.034	PD/CA		VA05070531	1.53

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2006	PAGE 5 of 12	
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	137.70-152.40	137.70	152.40	GND continuously changes from relatively unalt'd GND. Carb alt'n have sharp contacts with GND. Contacts commonly have slip surfaces. At 137.70m slickenlines at 80°, at 141.73 m with lines at 85°, at 142.00m, lines at 85°, @147.83m lines at 85°, at 148.90m lines at 60°, at 150.78m with lines at 75°. Carb alt'd core is softer and lighter in colour - locally intensely alt'd to carb/clay. Py smearing on slip faces. Minimal limonite on frac'd core. Most qtz vn's are < 1cm wide.					4	
10		152.40	165.49	Grey, relatively unaltered GND with multiple near parallel quartz veins; Qtz vns are thicker but do not contain much sulphides; Sericite alteration selvages are common among thicker (>2cm) veins; Only one occurrence of pyrite vein surrounded by 3cm sericite selvage occurring along fracture; Fractures commonly associated with thick (~3cm) sericite selvages; Slickenlines also common; At 155.55m = Face at 40° with lines at 45° TCA; At 156.67m = face at 45° with lines at 60° TCA: At 156.88m = face at 45° with lines at 80° TCA: At 161.40m = face at 60° with lines at 75° TCA; Local carbonate "fault gouge"(?) at 159.1m and 60°.		1			1	
10		165.49	181.36	Carbonate altered GND; GND is softer and lighter color; Local intervals of sericite alteration (166.32 - 167.64m); Short local intervals of mostly unaltered GND; Sericite alteration also occurs as selvages for fractures; Quartz veining is minimal but dominantly 45° TCA; Abundant factures with slickenlines preserved at.....165.70m = Fractured at 70° and lines at 85°; At 166.0m = fractured at 30° and lines at 45°; At 167.5m = fractured at 10° with lines at 70°; At 168.6m = fractured at 30° with lines at 55°; At 169.75m = fractured at 60° with lines at 70°; At 174.2m = fractured at 30° with lines at 40°; At 176.0m = fractured at 45° with lines at 70°; At 177.1m = fractured at 45° with lines at 80° TCA; At 179.12m = fractured at 40° with lines at 45° TCA; At 181.0m = fracture foliation at 60° with lines at 60°.		1			3	
10		181.36	191.04	Grey GND with minor to moderate carbonate alteration throughout; Sericite alteration is also apparent in short intervals (30cm); Multiple slip faces.....At 182.18m = fracture foliation at 45° with slickinlines at 70°; At 185.63m = fol'n at 45° with lines at 65°; At 186.13m = fol'n at 10° with lines at 10°; At 186.75m = fol'n at 60° with lines at 75°; At 188.88m = fol'n at 50° with lines at 70°; At 190.4m fol'n at 40° with lines at 90° TCA.		1			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
																						B363410	STANDARD 4D		0.455	4D		VA05070531	
6	1	1.0	2.5	45	30	1.0	s/q	3			2.0		0.1						2.0			B363411	135.64	137.70	0.032			VA05070531	2.06
1	1	1.0	1.0	45							2.0		1.0									B363412	137.70	138.68	0.041			VA05070531	0.98
5	1	2.0	5.5	45	60	0.5	q	5			1.0	0.1						2.0				B363413	138.68	140.21	0.031			VA05070531	1.53
1	6	0.5	0.5	45							30.0		10.0					5.0	5.0										
5	1	1.5	4.5	45							2.0		1.0									B363414	140.21	141.73	0.033			VA05070531	1.52
1	1	1.0	1.0	45							1.0							1.0				B363415	141.73	143.26	0.019			VA05070531	1.53
																						B363416	BLANK		<0.005			VA05070531	
4	1	0.5	1.5	30	45	0.5	Q/S	4			1.0		2.0						2.0			B363417	143.26	144.78	0.031			VA05070531	1.52
5	1	1.0	3.0	45	30						1.0		1.0					1.0	1.0			B363418	144.78	146.30	0.024			VA05070531	1.52
1	1	1.0	1.0	45							2.0							1.0	1.0			B363419	146.30	147.83	0.039			VA05070531	1.53
0																						B363420	147.83	149.35	0.015			VA05070531	1.52
2	6	1.0	1.5	45		0.5	Q/S	3			50.0		10.0					10.0				B363421	149.35	150.88	0.096			VA05070531	1.53
2	6	1.0	1.5	45		0.5	Q/S	3			50.0		10.0					10.0				B363422	149.35	150.88	0.039	DUP		VA05070531	
1	1	0.5	0.5	30							0.1		0.1									B363423	150.88	152.40	0.014			VA05070531	1.52
7	1	2.0	9.0	45		1.0	q/s	4			2.0	1.0	1.0						1.0			B363424	152.40	153.92	0.023			VA05070461	1.52
5	1	3.0	9.0	45		2.0	s/chl	5		0.1	3.0	0.1	2.0						1.0			B363425	153.92	155.45	0.065			VA05070461	1.53
8	1	3.0	9.0	45		1.0	q/s	5			2.0	0.1	1.0						1.0			B363426	155.45	156.97	0.068			VA05070461	1.52
1	6	0.5	0.5	45		3.0	s	5		70.0								30.0											
9	1	3.5	12.5	45		2.0	s/q	4			2.0	0.1										B363427	156.97	158.50	0.218			VA05070461	1.53
15	1	4.0	23.0	45		1.0	q/s	5			1.0	0.1					0.1		0.1			B363428	158.50	160.10	0.112		trace Mo	VA05070461	1.60
15	1	4.0	23.0	45		1.0	q/s	5			1.0	0.1					0.1		0.1			B363429	158.50	160.10	0.098	PD/CA		VA05070461	1.60
																						B363430	STANDARD 5E		1.545	5E		VA05070461	
5	1	1.0	2.5	45		1.0	s/q	4		0.1	1.0											B363431	161.10	161.54	0.026			VA05070461	0.44
7	1	1.0	3.0	45		1.0	q				1.0		0.1									B363432	161.54	163.07	1.835			VA05070461	1.53
4	1	1.0	4.0	45	30	2.0	s/q	4			2.0		0.1									B363433	163.07	164.59	0.831			VA05070461	1.52
1	1	3.0	3.0	30		6.0	s/chl	5		7.0	10.0	1.0	1.0									B363434	164.59	164.90	2.55			VA05070461	0.31
0																						B363435	164.90	165.49	0.008			VA05070461	0.59
																						B363436	BLANK		<0.005			VA05070461	
0																						B363437	165.49	166.32	0.035			VA05070461	0.83
1	1	1.5	1.5	60						4.0												B363438	166.32	167.64	0.199			VA05070461	1.32
1	3	1.0	1.0	5																									
0																						B363439	167.64	169.16	0.057			VA05070461	1.52
1	1	1.0	1.0	45							2.0											B363440	169.16	170.69	0.02			VA05070461	1.53
1	1	1.0	1.0	45																		B363441	170.69	172.21	0.054			VA05070461	1.52
1	6	0.3	0.3	45						30.0	20.0		2.0									B363442	170.69	172.21	0.082	DUP		VA05070461	1.52
3	1	1.0	1.0	45							2.0											B363443	172.21	173.74	0.025			VA05070461	1.53
3	1	1.0	1.0	45							2.0											B363444	173.74	175.26	0.062			VA05070461	1.52
1	1	7.0	7.0	50		0.5	s	3		3.0	1.0		4.0					1.0	1.0			B363445	175.26	176.78	0.203			VA05070461	1.52
0																						B363446	176.78	178.31	0.012			VA05070461	1.53
1	1	2.0	3.0	30		1.0	q	4			5.0		2.0									B363447	178.31	179.83	0.046			VA05070461	1.52
3	1	1.0	3.0	45							2.0											B363448	179.83	181.36	0.015			VA05070461	1.53
3	1	1.0	3.0	45							2.0											B363449	179.83	181.36	0.016	PD/CA		VA05070461	1.53
																						B363450	STANDARD 2B		3.12	2B		VA05070461	
4	1	2.5	7.0	45							10.0		5.0									B363451	181.36	182.88	2.38			VA05070461	1.52
2	6	0.5	1.0	45		1.0	s/q	5			40.0		10.0						5.0										

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2005	PAGE 7 of 12	
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		191.04	195.07	Core is altered to a creamy pale green color; Sharp contact between unaltered and altered core at 45° TCA; Irregular veins of K-spar (creamy peach color) are abundant throughout (mostly mm-scale but up to 1cm); Core is speckled with anhedral to subhedral K-spar grains throughout; Along fracture and slip faces, darker green (chlorite altered?) pyrite commonly associated with fractures (v.f.gr. blebs) and smeared on faces; Pyrite in fractures found with grey clay matrix (ox'd sulphides); Sericite alteration is dominant throughout; Quartz veining is minimal; Fracturing at 193.25m = face at 50° with slickenlines at 60°; At 194.1m = Face at 10° with slickenlines at 60°.						
10		195.07	212.20	Grey GND with minor carbonate filled fractures; Local sericite alteration around fractures; At 199.64m = Rounded MSED clasts (rounded by drill), most likely cavings; At 209 - 209.25m = Intensely altered to green clay with quartz eyes; Pyrite common on slip faces (+ graphite?); Fractures at 195.8m = Fracture foliation at 30° with slickenlines at 40° TCA; At 198.0m = Fract fol'n at 65° with Slickinlines at 65°; At 205.11m = Fract fol'n at 30° with slickinlines at 30° TCA.		1			1	
11		121.20	216.87	Dark grey GND; Fine grained and softer than previous grey GND; Appears unaltered; At 212.67m - 212.70m = Intrusion of biotite poor GND (felsic?) with sharp contacts at 60°; Qtz veining is minimal (no vein >1cm); Fracturing common with chloritic (?) slickenlines; Sharp contact with felsic GND at 60°; Fractures: at 213.4m = Fracture foliation at 20° with slickenlines at 30°; At 213.88m = Fract fol'n at 45° with 50° lines; At 216.46m = Fract fol'n at 60° with lines at 70°.		1			2	
10		216.87	229.92	Grey GND with moderate to low quartz veining; Locally core is sericite altered (mod) up to 50cm; Low carbonate alteration also occurs (up to 50cm) giving core a lighter appearance and making it softer; Pyrite often occurs smeared on slip faces with chlorite; Where GND is slightly carbonate altered, quartz veining is very minimal; At 221.19m = sulphide vein with pyrrhotite and biotite with slight chlorite alteration (0.5cm); Fracture faces (foliation) with slickenlines: At 219.80m = 60°/70°; At 223.13m = 10°/30°; At 224.24m = 50°/50°; At 229.02m = 45°/45°.		2			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	2.0	6.0	45						5.0	1.0		1.0									B363452	182.88	184.40	0.16			VA05070461	1.52
1	6	0.5	0.5	45						20.0								50.0											
0	1	1.5	6.0	45							2.0											B363453	184.40	185.93	0.104			VA05070461	1.53
3	1	1.0	3.0	45						0.1	1.0											B363454	185.93	187.45	0.058			VA05070461	1.52
6	1	1.5	5.0	45		0.4	q	4			3.0											B363455	187.45	188.98	0.103			VA05070461	1.53
																						B363456	BLANK		<0.005			VA05070461	
5	1	2.0	5.0	45							2.0		0.1									B363457	188.98	190.50	0.074			VA05070461	1.52
1	6	1.0	1.0	45		1.0	q	4			50.0		10.0																
1	1	2.0	2.0	45		0.5	q	3			1.0											B363458	190.50	191.04	0.053			VA05070461	0.54
3	1	1.0	2.5	45							1.0											B363459	191.04	192.02	0.018			VA05070461	0.98
1	1	1.0	1.0	45						0.1												B363460	192.02	193.55	0.011			VA05070461	1.53
2	1	1.0	2.0	45							0.1											B363461	193.55	195.07	0.033			VA05070461	1.52
2	1	1.0	2.0	45							0.1											B363462	193.55	195.07	0.028	DUP		VA05070461	1.52
3	1	1.0	2.5	45		1.0	q	4		1.0	1.0											B363463	195.07	196.60	0.059			VA05070461	1.53
5	1	2.0	4.5	45							5.0	0.1										B363464	196.60	198.12	0.063			VA05070461	1.52
1	1	1.0	1.0	45							1.0											B363465	198.12	199.64	0.03		2cm vein wi 25% pyrrho	VA05070461	1.52
2	1	2.0	4.0	45							1.0											B363466	199.64	201.17	0.026			VA05070461	1.53
2	1	1.5	25.0	45							1.0											B363467	201.17	202.69	0.012			VA05070461	1.52
2	1	2.0	3.0	45							1.0	0.1										B363468	202.69	204.22	0.44			VA05070461	1.53
2	1	2.0	3.0	45							1.0	0.1										B363469	202.69	204.22	0.036	PD/CA		VA05070461	1.53
																						B363470	STANDARD 3C		0.092	3C		VA05070461	
0																						B363471	204.22	205.74	0.017			VA05070461	1.52
2	1	1.0	1.5	45						1.0	2.0											B363472	205.74	207.26	0.048			VA05070461	1.52
2	6	0.3	0.6	45						80.0												B363473	207.26	208.79	0.024			VA05070461	1.53
																						B363474	208.79	209.30	0.229			VA05070461	0.51
																						B363475	209.30	209.72	0.054			VA05070461	0.42
																						B363476	BLANK		<0.005			VA05070461	
3	1	2.0	5.0			1.0	s	4		1.0	1.0											B363477	209.72	210.45	0.152			VA05070461	0.73
1	6	0.7	0.7							70.0								10.0											
3	1	1.0	3.0	45	60	0.2	q	4			1.0		1.0									B363478	210.45	212.21	0.026			VA05070461	1.76
2	1	1.0	1.5	30	60																	B363479	212.21	213.36	0.347			VA05070461	1.15
1	1	0.8	0.8	45						1.0	2.0											B363480	213.36	214.88	0.035			VA05070461	1.52
1	6	0.5	0.5	45							50.0											B363481	214.88	216.41	0.006			VA05070461	1.53
1	6	0.5	0.5	45							50.0											B363482	214.88	216.41	0.019	DUP		VA05070461	1.53
2	1	0.3	0.5	45						1.0	1.0											B363483	216.41	216.87	0.023			VA05070461	0.46
3	1	2.0	4.0	45	1					5.0												B363484	216.87	217.93	0.547			VA05070461	1.06
1	4	2.0	2.0	45																									
4	1	2.0	5.0	45		1.0	q/chl	4		0.1	2.0											B363485	217.93	219.46	0.108			VA05070461	1.53
1	1	1.0	1.0	45							0.1											B363486	219.46	220.98	0.015			VA05070461	1.52
5	1	1.5	6.0	45	60						2.0											B363487	220.98	222.50	0.046			VA05070461	1.52
1	6	0.5	0.5	135							40.0									50.0									
2	1	2.0	4.0	50							2.0											B363488	222.50	224.03	0.073			VA05070461	1.53
1	4	2.0	2.0	45																									
2	1	2.0	4.0	50							2.0											B363489	222.50	224.03	0.047	PD/CA		VA05070461	1.53
1	4	2.0	2.0	45																									
																						B363490	STANDARD 5E		1.5	5E		VA05070461	
1	1	0.5	0.5	45							2.0											B363491	224.03	225.55	0.037			VA05070461	1.52
2	1	3.0	4.0	45						1.0	2.0		0.1									B363492	225.55	227.08	0.088			VA05070461	1.53

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2005	PAGE 4 of 12	
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.65	250.50	Green GND; Interval displays varying degrees of alteration from intense and crumbly core (234.93 - 236.22m); Carbonate veinlets +/- blebs are common throughout interval and locally caused minor alteration; Carbonate has creamy appearance; Near 3cm v.f.gr. aspy (dirty) vn are euhedral aspy grains (3x5mm); Pyrite common on slip faces - slip parallel to quartz veins have pyrite smeared along vein of slip face.		4			1	
10		250.50	266.70	Back into grey unaltered GND (locally very slightly carbonate altered - up to 20cm); Core is slightly more felsic in places; Quartz veining in minimal-moderate; Core is moderately fractured.					1	
10		266.70	277.18	Abundant sericite alteration due to fracturing in GND: Low amount of quartz veining; One large quartz vein at 272.17m (7cm); Also minor carbonate alteration and fracture filling throughout; Intense sericite alteration (crumbly) from 276.5 - 277.18m; Slickenlines are present at 270.5m at 65°; At 273.71m at 80° TCA.		4			1	
10		277.18	292.10	Mostly unaltered grey GND; Local intervals of slightly sericite and carbonate altered GND; Slight color change for sericite alteration; Slickenlines: at 277.37m = 60°; At 281.8m = 45°; At 288.86m = 10°.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides										Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other		From	To					
3	1	4.0	7.0	45	0	0.5	q	5			1.0											B363493	227.08	228.60	0.337			VA05070461	1.52
3	1	1.0	2.0	45	10	0.2	q	5			2.0											B363494	228.60	229.92	0.033			VA05070461	1.32
0																						B363495	229.92	231.65	0.101			VA05070461	1.73
																						B363496	BLANK		0.049			VA05070461	
2	6	3.0	3.2	45		2.0	q/chl	5		1.0	10.0		90.0					10.0				B363497	231.65	233.17	<0.005			VA05070461	1.52
1	1	0.5	0.5	45							2.0																		
1	1	0.3	0.3	45									1.0									B363498	233.17	234.92	0.062			VA05070461	1.75
0																						B363499	234.92	236.22	0.045			VA05070461	1.30
2	4	0.4	0.7	30																		B363500	236.22	237.74	0.051			VA05070461	1.52
1	1	0.4	0.4	45							1.0							1.0											
2	1	1.5	2.0	60		0.2	q	5										1.0				B363501	237.74	239.27	0.032			VA05070461	1.53
2	4	1.0	1.5	30														1.0											
2	1	1.5	2.0	60		0.2	q	5										1.0				B363502	237.74	239.27	0.028	DUP		VA05070461	1.53
2	4	1.0	1.5	30														1.0											
2	1	0.5	1.0	45																		B363503	239.27	240.79	0.015			VA05070461	1.52
0																						B363504	240.79	241.69	0.076			VA05070461	0.90
3	1	4.0	10.0	60						2.0												B363505	241.69	242.32	0.084			VA05070461	0.63
1	1	0.5	0.5	60							1.0							1.0				B363506	242.32	243.84	0.026			VA05070461	1.52
3	1	1.0	2.0	45							2.0											B363507	243.84	245.36	0.033			VA05070461	1.52
1	1	1.0	1.0	45							1.0											B363508	245.36	246.89	0.019			VA05070461	1.53
																						B363509	245.36	246.89	0.015	PD/CA		VA05070461	1.53
																						B363510	STANDARD 4D		0.427	4D		VA05070461	
2	1	3.0	3.5	45	60	2.0	q/chl	5			0.1											B363511	246.89	248.32	0.029			VA05070461	1.43
1	4	0.5	0.5	70														1.0											
0																						B363512	248.32	248.90	0.031			VA05070461	0.58
4	1	3.0	6.0	45		5.0	5	5		1.0	1.0											B363513	248.90	250.50	0.047			VA05070461	1.60
0																						B363514	250.50	251.46	0.007			VA05070461	0.96
5	1	1.0	4.0	60	45	0.3	1	5			1.0							2.0	1.0			B363515	251.46	252.98	0.017			VA05070461	1.52
																						B363516	BLANK		<0.005			VA05070461	
0																						B363517	252.98	254.51	0.009			VA05070461	1.53
2	1	11.0	12.0	45						0.1	0.1											B363518	254.51	256.03	0.098			VA05070461	1.52
2	1	1.0	2.0	45		0.1	q	5			2.0											B363519	256.03	257.56	0.017			VA05070461	1.53
3	1	1.0	1.7	60	45	0.4	q	5		1.0	2.0	0.1	0.1									B363520	257.56	259.08	0.072			VA05070461	1.52
1	1	1.0	1.0	45							10.0								1.0			B363521	259.08	260.60	0.057			VA05070461	1.52
1	1	1.0	1.0	45							10.0								1.0			B363522	259.08	260.60	0.037	DUP		VA05070461	1.52
0																						B363523	260.60	262.13	0.041			VA05070461	1.53
2	1	1.5	1.8								1.0		1.0				0.1					B363524	262.13	263.65	0.025		Trace Mo	VA05070461	1.52
0																						B363525	263.65	265.18	0.035			VA05070461	1.53
2	1	0.5	1.0	45							1.0											B363526	265.18	266.70	0.043			VA05070461	1.52
2	1	2.5	3.0	45		0.3	q	5			1.0											B363527	266.70	268.22	0.336			VA05070461	1.52
1	6	0.2	0.2	45									90.0					5.0											
1	1	0.8	0.8	45							1.0											B363528	268.22	269.75	0.019			VA05070461	1.53
																						B365968	268.22	269.75	0.019	DP_ORIG	Old: B363528		1.53
																						B365969	268.22	269.75	0.018	PD	Old: B363529		
5	1	1.0	2.2	45							2.0		1.0				0.1					B365970	STANDARD 1A		0.978	1A	Old: B363530 Trace Mo		
2	1	7.0	7.5	45							0.1		0.1									B365971	269.75	271.40	0.025		Old: B363531		1.65
0																						B365972	271.40	272.24	0.064		Old: B363532		0.84
0																						B365973	272.24	273.81	0.034		Old: B363533	VA05070461	1.57
																						B363534	273.81	274.91	0.016				
1	1	0.5	0.5	45							0.1											B363535	274.91	276.35	0.011			VA05070461	1.44
																						B363536	BLANK		<0.005			VA05070461	
0																						B363537	276.35	277.18	0.013			VA05070461	0.83
2	1	0.5	0.8	45	60						2.0							1.0				B363538	277.18	278.98	0.005			VA05070461	1.80
4	1	2.0	5.0	45	60						2.0							2.0				B363539	278.98	280.42	0.012			VA05070461	1.44
0																						B363540	280.42	281.94	0.04			VA05070461	1.52
3	1	2.0	3.0	45							2.0		1.0						1.0			B363541	281.94	283.46	0.018			VA05070461	1.52

DRILL LOG LEGEND P1	DATE: July 26th to 30th, 2006 PAGE 11 of 12		
DRILL HOLE # : DG05-299C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		292.10	294.14	GND: Intense sericite alteration; Minimal quartz veining; Highly fractured; Slickenlines at 60° at 294.1m		5				
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: July 26th to 30 th, 2005

LOGGED BY: Kevin Peipgrass

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
2	4	0.5	1.0	45																									
3	1	2.0	3.0	45							2.0		1.0						1.0			B363542	281.94	283.46	**0.009**	DUP		VA05070461	1.52
2	4	0.5	1.0	45																									
1	4	0.5	0.5	45																		B363543	283.46	284.99	**0.015**			VA05070461	1.53
1	1	0.5	0.5	30							2.0											B363544	284.99	286.51	**0.011**			VA05070461	1.52
1	1	0.5	0.5	30						2.0	10.0											B363545	286.51	288.04	**1.375**			VA05070461	1.53
1	3	0.5	0.5	30							2.0																		
1	1	0.5	0.5	45							1.0											B363546	288.04	289.56	**0.013**			VA05070461	1.52
4	1	0.6	1.5	45							3.0											B363547	289.56	291.08	**0.028**			VA05070461	1.52
1	1	0.6	0.6	45							2.0							2.0				B363548	291.08	292.10	**0.122**			VA05070461	1.02
																						B363549	291.08	292.10	**0.104**	PD/CA		VA05070461	1.02
																						B363550	STANDARD 1A		**3.31**	1A		VA05070461	
2	3	0.5	1.0	45	30								2.0						2.0			B363551	292.10	293.37	**0.012**			VA05070461	1.27
1	1	1.0	1.0	30		1.0	chl	3			4.0											B363552	293.37	294.14	**0.051**			VA05070461	0.77

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-300C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 959m

BEARING: 000 | DIP: -50°

DATE STARTED: 27-Jul-05 | DATE COMPLETED: 31-Jul-05

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459560 NORTHING: 7099188

COORD SYSTEM: NAD 83: EASTING: 459441 NORTHING: 7099373

NAD 27 (CORRECTED for historic grid): EASTING: 459530 NORTHING: 7099198

SECTION LINE(historic grid): 459525 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 7.92m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	7.92	Casing
7.92	246.89	GND (with intervals of MGD)

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B363553 - B363623

Requisition #: MASP448STRGOL.05Q | Date Shipped: 19-Aug-05

Lab Record #: VA05072072 | Date Received: 25-Aug-05

Sample Sequence: B363624-B363742

Requisition #: MASP448STRGOL.05Q | Date Shipped: 26-Aug-05

Lab Record #: VA05074728 | Date Received: 1-Sep-05

Sample Sequence: B363743 - B363772

Requisition #: MASP448STRGOL.05Q | Date Shipped: 29-Aug-05

Lab Record #: VA05074737 | Date Received: 2-Sep-05

Duplicates:	363563; 363583; 363602; 363622; 363642; 363662; 363682; 363702; 363722; 363742; 363762
Preparation Duplicate/ Check Assay:	363569; 363589; 363609; 363629; 363649; 363669; 363689; 363709; 363729; 363749; 363769
Standards:	363570 (5E); 363590 (3C); 363610 (6F); 363630 (2B); 363650 (6F); 363670 (5E); 363690 (6F); 363710 (4D); 363730 (1A); 363750 (6F); 363770 (3C)
Blanks:	363556; 363576; 363596; 363616; 363636; 363656; 363676; 363696; 363716; 363736; 363756

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	335.20	-50.20	1.20	2.20
121.92	329.50	-50.80	355.50	356.50
246.89	337.50	-51.50	3.50	4.50

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: August 14-20th 2005	PAGE 1 of 12	
DRILL HOLE # : **DG05-300C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 4.88	0.00	4.88	Casing - no recovery						
10	4.88 - 68.86	4.88	38.24	GND: GND is highly fractured and broken up with limonite on all surfaces; Oxidations is also present throughout GND; Locally competent core (up to 21cm pieces) at 30.68m; 95% of core is too broken up to recover vein info; Generally low recovery throughout interval; Possible fault gouge at end of interval (37.5 - 37.8m) made up of limonitic clay, very crumbly; Slickensides present at 24.45m at 45° TCA, at 34.95m at 45° TCA.	4					
10		38.24	51.00	GND is extremely oxidized; Oxidation appears to be large selvages (up to 20cm); Small - 2cm selvages also present; Oxidation selvages are also carbonate altered; Possible sericite alteration in less oxidized core (rusty green color); Core moderately broken up; Only minor quartz veining; Completely oxidized sulphide veins are present at 55m; FAULT GOUGE present from 46.95 - 47.35m, Sharp contact with oxidized GND with slickenlines at 85° TCA; Slickenlines at 49.8m at 70° TCA.	5					
10		51.00	58.84	GND is oxidized to a much lesser degree - only present along fractures and locally minor oxidation throughout, also small (1cm) weak limonite selvages; 40cm interval of highly fracture core (3x3x3 cm pieces - average); Quartz veining still low; Core switch because slightly softer and paler GND to Grey GND (~1m intervals) with sharp contacts; Sulphides in quartz veins have been leached out, leaving vugs (52.07m); Slickensides: at 55.55m = 70° TCA.	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 14-20th, 2005

LOGGED BY: K Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																													
						Selvages				Sulphides										Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B363553	4.88	6.10	0.013			VA05072072	1.22
0																						B363554	6.10	7.67	0.009			VA05072072	1.57
1	1	0.3	0.3	45														3.0				B363555	7.67	9.14	0.045			VA05072072	1.47
																						B363556	BLANK		<0.005			VA05072072	
0																						B363557	9.14	10.67	0.009			VA05072072	1.53
0																						B363558	10.67	12.14	0.027			VA05072072	1.47
0																						B363559	12.14	13.72	0.025			VA05072072	1.58
0																						B363560	13.72	15.24	0.041			VA05072072	1.52
0																						B363561	15.24	16.76	0.018			VA05072072	1.52
0																						B363562	15.24	16.76	0.027	DUP		VA05072072	1.52
0																						B363563	16.76	19.81	0.038			VA05072072	3.05
0																						B363564	19.81	21.34	0.008			VA05072072	1.53
1	1	0.5	0.5	45														2.0				B363565	21.34	22.86	0.018			VA05072072	1.52
0																						B363566	22.86	24.38	0.031			VA05072072	1.52
0																						B363567	24.38	25.91	0.046			VA05072072	1.53
0																						B363568	25.91	27.43	0.056			VA05072072	1.52
0																						B363569	25.91	27.43	0.059	PD/CA		VA05072072	1.52
																						B363570	STANDARD 5E		1.445	5E		VA05072072	
0																						B363571	27.43	28.96	0.016			VA05072072	1.53
0																						B363572	28.96	30.48	0.089			VA05072072	1.52
0																						B363573	30.48	32.00	0.169			VA05072072	1.52
0																						B363574	32.00	33.53	0.028			VA05072072	1.53
1	1	1.0	1.0	35														5.0				B363575	33.53	35.05	0.047			VA05072072	1.52
																						B363576	BLANK		<0.005			VA05072072	
0																						B363577	35.05	36.58	0.026			VA05072072	1.53
2	1	0.5	1.0	60								0.1						10.0				B363578	36.58	38.10	0.016			VA05072072	1.52
																						B363579	38.10	39.62	0.036			VA05072072	1.52
0																						B363580	39.62	41.15	0.093			VA05072072	1.53
0																						B363581	41.15	42.67	0.738			VA05072072	1.52
0																						B363582	41.15	42.67	0.014	DUP		VA05072072	1.52
0																						B363583	42.67	44.20	0.132			VA05072072	1.53
1	1	0.4	0.4	60														10.0				B363584	44.20	45.72	0.280			VA05072072	1.52
0																						B363585	45.72	46.95	0.031			VA05072072	1.23
0																						B363586	46.95	47.35	0.146			VA05072072	0.40
2	1	0.4	0.8	40		2.0	s/q	5	4	2.0								5.0				B363587	47.35	48.77	0.027			VA05072072	1.42
1	4	0.4	0.4	50																											
2	6	0.4	0.8	60						5.0								95.0				B363588	48.77	50.29	0.099			VA05072072	1.52
2	6	0.4	0.8	60						5.0								95.0				B363589	48.77	50.29	0.097	PD/CA		VA05072072	1.52
																						B363590	STANDARD 3C		0.086	3C		VA05072072	
0																						B363591	50.29	51.00	0.035			VA05072072	0.71
0																						B363592	51.00	51.82	0.295			VA05072072	0.82
1	1	1.0	1.0	50						0.1								20.0				B363593	51.82	53.35	0.206			VA05072072	1.53
0																						B363594	53.35	54.86	0.037			VA05072072	1.51
1	1	1.0	1.0	25						1.0			2.0					50.0				B363595	54.86	56.39	0.058			VA05072072	1.53
																						B363596	BLANK		<0.005			VA05072072	
1	1	0.5	0.5	50														10.0				B363597	56.39	57.91	0.068			VA05072072	1.52
0																						B363598	57.91	58.84	0.086			VA05072072	0.93

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 3 of 12	
DRILL HOLE # : **DG05-300C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		58.84	61.33	GND: Back to very limonitic GND with overprinted sericite +/- chlorite alteration within oxidized selvages; Sulphide vein at 59.83m contains 50% fresh, fine grained pyrite; Fresh fine grained euhedral pyrite inside vugs (up to 0.2x0.4cm vugs) of quartz veins are present.	5					
10		61.33	64.01	GND: Back into less oxidized GND with limonite on fractures as previously described; Vuggy quartz veins still present with limonite staining inside and fresh euhedral fine grained pyrite.						
10		64.01	68.86	GND: Highly fractured with intervals up to 30cm of competent core; Limonite on/in carbonate lined fractures and opened faces; GND appears slightly more mafic here (?); Quartz veins contain vugs (5x3x4mm); Slickenlines: at 64.01m = 70° TCA; At 66.23m = 60° TCA.	3					
30	68.86 - 74.08	68.86	74.08	GND: GND has higher percentage of biotite, giving it a much darker appearance (mafic?); Minor quartz veining; Large quartz veins have sericite alteration selvages; From 68.86m - 69.52m = intense sericite alteration with large 5x6cm blebs of quartz with carbonate fractures; From 71.0 - 71.5m = Highly fractured MGD (3.5 x 5 x 2 cm avg) with calcite and some limonite on fractures; Slickenlines: at 70.11m = 60° TCA; At 73.35m = 30° TCA.		1				
10	74.08 - 80.92	74.08	80.92	Grey GND with no apparent alteration; Local carbonate alteration from 75.90 - 76.23m; Majority of quartz veins have quartz selvages; MGD interval with sharp contact from 77.02 - 77.16m at 30° TCA; Pyrite common in carbonate fracture filling.					1	
30	80.92 - 88.39	80.92	88.39	MGD (More mafic GND): Back into MGD as prev. description; Quartz veins commonly have quartz flooded selvages; Frequent carbonate fracture filling; Slickenlines: at 84.15m = 45°; At 81.37m = 45° TCA.						
10	88.39 - 91.62	88.39	91.62	GND: Has been altered to a greyish green colour (sericite) to a deeper green color (chlorite?); Chlorite altered GND is much softer and is crumbly whereas ser altered GND is much more competent (retained silica); Carbonate fracture filling is abundant throughout; Quartz veining is minimal, but tends to be thicker (~4cm) with low sulphide content.		5	5	1		
10		91.62	93.96	GND: GND is light in color with high carbonate content = carbonate alteration; Interval is very crumbly; High k-spar content (cream color); K-spar is very soft; Minimal quartz veining with sericite/chlorite selvages (~1m) slickenlines present on broken core.		2		2	4	2
30		93.96	99.49	MGD: Back into MGD as seen in 66.86 - 74.08m; Quartz veining is more abundant; Carbonate fracture filling abundant; Core moderately broken up.						

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 4 of 12
Selvages 0 = No Alteration 5 = Intense Alt'n	**Ox. State** 0 = No Oxidized Sulphides 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass
Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ec = calcite		
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz		

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
2	1	0.4	0.6	50		2.0	q/s	5	3	2.0												B363599	58.84	59.94	0.165			VA05072072	1.10
1	6	0.4	0.4	60		3.0	q/s	5	3	50.0																			
3	1	0.5	1.5	60	45					2.0			3.0					5.0				B363600	59.94	61.33	0.210			VA05072072	1.39
0																						B363601	61.33	62.58	0.031			VA05072072	1.25
0																						B363602	61.33	62.58	0.033	DUP		VA05072072	1.25
1	1	0.5	0.5	60									2.0					5.0				B363603	62.58	64.01	0.253			VA05072072	1.43
2	1	0.3	0.5	30	60	0.5	1	5			2.0		3.0									B363604	64.01	65.53	0.190			VA05072072	1.52
2	1	1.0	1.5	40	60					2.0	1.0		2.0					5.0				B363605	65.53	67.06	0.105			VA05072072	1.53
3	1	1.0	2.2	45						1.0			1.0					2.0				B363606	67.06	68.86	0.048			VA05072072	1.80
4	1	1.0	4.0	45	60	5.0	s	5		2.0	2.0		2.0					5.0				B363607	68.86	70.10	0.460			VA05072072	1.24
3	1	1.0	25.0	30																		B363608	70.10	71.63	0.033			VA05072072	1.53
3	1	1.0	25.0	30																		B363609	70.10	71.63	0.024	PD/CA		VA05072072	1.53
																						B363610	STANDARD 6F		2.730	6F		VA05072072	-
1	1	0.6	0.6	45						1.0												B363611	71.63	73.15	0.025			VA05072072	1.52
2	1	2.0	2.5	45		4.0	s/cb				4.0								2.0			B363612	73.15	74.08	0.072			VA05072072	0.93
7	-	1.6	3.3	30	50	0.5	q	5			2.0							1.0				B363613	74.08	75.90	0.515			VA05072072	1.82
1	3	0.5	0.5	60																		B363614	75.90	76.23	0.077			VA05072072	0.33
7	1	1.0	4.5	45	60	0.4	q	s			5.0	1.0	2.0									B363615	76.23	77.72	0.125			VA05072072	1.49
																						B363616	BLANK		<0.005			VA05072072	
4	1	0.5	2.0	45	60	0.4	q	5			5.0		1.0									B363617	77.72	79.25	0.231			VA05072072	1.53
2	1	0.5	0.9	45	55	0.3	q	s			25.0											B363618	79.25	80.92	0.114			VA05072072	1.67
1	3	1.0	1.0	45		0.2	q	5			50.0											B363619	80.92	82.30	0.064			VA05072072	1.38
1	3	0.2	0.2	45						1.0	1.0																		
8	1	2.0	6.0	45	60	1.5	s	5		1.0	2.0	1.0										B363620	82.30	83.82	0.263			VA05072072	1.52
2	1	0.5	1.0	45							2.0											B363621	83.82	85.34	0.091			VA05072072	1.52
1	5	0.4	0.4	30																									
2	1	0.5	1.0	45							2.0											B363622	83.82	85.34	0.116	DUP		VA05072072	1.52
1	5	0.4	0.4	30																									
4	1	1.0	2.5	60	30						2.0											B363623	85.34	86.87	0.299			VA05072072	1.53
1	6	0.2	0.2	45							50.0																		
4	1	1.0	3.0	45							2.0											B363624	86.87	88.39	0.199			VA05074728	1.52
2	1	4.0	5.0	45									0.1									B363625	88.39	89.86	0.178			VA05074728	1.47
0																						B363626	89.86	90.38	0.113			VA05074728	0.52
1	1	4.0	4.0	45		29.0	chl	5		2.0	1.0		0.1									B363627	90.38	91.10	0.085			VA05074728	0.72
1	1	1.0	1.0	45						1.0	1.0		1.0									B363628	91.10	91.62	0.197			VA05074728	0.52
1	1	1.0	1.0	45						1.0	1.0		1.0									B363629	91.10	91.62	0.112	PD/CA		VA05074728	0.52
																						B363630	STANDARD 2B		3.210	2B		VA05074728	
2	1	1.0	1.5	45		0.5	s/chl	4		1.0	2.0		3.0									B363631	91.62	92.96	0.174			VA05074728	1.34
3	1	1.0	2.0	45		0.5	s/chl	4			2.0		0.1									B363632	92.96	93.96	0.229			VA05074728	1.00
1	5	0.5	0.5	30						1.0	1.0																		
4	1	1.0	2.5	45	8						1.0											B363633	93.96	95.40	0.382			VA05074728	1.44
3	1	2.0	3.0	45		1.0	s/chl	4		1.0	5.0	1.0	1.0									B363634	95.40	96.86	0.185			VA05074728	1.46
1	1	1.0	1.0	30																		B363635	96.86	98.08	0.152			VA05074728	1.22
																						B363636	BLANK		0.013			VA05074728	
1	1	1.0	1.0	40																		B363637	98.08	99.49	0.222			VA05074728	1.41

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 5 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		99.49	105.65	GND: GND has become very felsic; MDG/GND contact distinct but crumbly; higher carbonate and k-spar content; Creamy k-spar is harder than interval 91.62 - 93.96m; Carbonate fracture filling has pale green hue (sericite); Quartz veining tends to be irregular +/- displaced or in blebs with carbonate fractures; Core is relatively soft; Slickenlines: at 99.69m on 10° face, lines at 10° TCA; At 102.0m on 20° face, lines at 85°; At 103.83m on 60° face, lines at 70° TCA; At 102.51m, on 0° face, lines at 70° TCA.		2	1	3	2	
10		105.65	124.97	GND: GND slightly darker (greyer) than previous (99.49 - 105.65m); Less abundant carbonate fractures; Less abundant k-spar; GND is also harder and less broken-up; Local sericite alteration (intensive) from 110.65m - 111.49m (largest interval), sharp contact with quartz vein at 45°; Local intensive carbonate alteration 106.76 - 106.97m and 109.92 - 110.14m; Quartz veining tends to be more abundant in sericite altered veins; <2mm qtz/chl/sulphide (po) veins are common; Chlorite + carb common on slip face with smeared pyrite; Slickenlines: at 113.3m on 30° face, lines at 60°; At 115.3m, face at 50° with lines at 50°; At 119.9m, face at 119.9m with lines at 70°; At 121.92m, face at 30° with lines at 60° TCA.		2	1	2	1	
10		124.97	147.83	GND: Grey GND; Very gradual change from previous interval (105.65 - 124.97m); GND is slightly darker; Carb and chlorite alteration are present on a majority of the fracture and slip faces - commonly with pyrite smearing; Pyrrhotite and arsenopyrite common in chl/s selvages; <1mm qtz+chl/cb/po veinlets common with quartz/ser selvages; Minor intervals of slightly more felsic (?) GND; Slickenlines: at 128.15m, face at 10° with lines at 45° TCA; At 135.8m, face at 45° with lines at 45° TCA; At 142.5m, face at 45° with lines at 60°.		2	2	2	2	

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 6 of 12
Selvages 0 = No Alteration 5 = Intense Alt'n	**Ox. State** 0 = No Oxidized Sulphides 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																	Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B363638	99.49	100.58	**0.459**			VA05074728	1.09
4	1	1.5	3.0	45	60	0.5	q/chl	3			0.1		0.1									B363639	100.58	102.11	**0.062**			VA05074728	1.53
3	1	1.0	2.0	45	30						1.0		1.0									B363640	102.11	103.63	**0.387**			VA05074728	1.52
2	1	1.5	2.0	45	30	1.0	q/chl	5														B363641	103.63	104.83	**0.782**			VA05074728	1.20
2	1	1.5	2.0	45	30	1.0	q/chl	5														B363642	103.63	104.83	**1.465**	DUP		VA05074728	1.20
4	1	0.4	1.5	45	30	0.5	q/chl	3			2.0		1.0									B363643	104.83	105.65	**4.910**			VA05074728	0.82
3	1	0.4	1.0	30	45						2.0											B363644	105.65	106.68	**0.194**			VA05074728	1.03
4	1	1.0	2.2	45	30	0.3	q/chl	5			2.0		2.0									B363645	106.68	108.20	**0.238**			VA05074728	1.52
3	1	0.3	0.8	45	30	0.5	q/chl	5			10.0		1.0									B363646	108.20	109.73	**0.328**			VA05074728	1.53
0																						B363647	109.73	110.53	**0.460**			VA05074728	0.80
4	1	0.5	2.0	45							2.0											B363648	110.53	111.50	**0.196**			VA05074728	0.97
4	1	0.5	2.0	45							2.0											B363649	110.53	111.50	**0.975**	PD/CA		VA05074728	0.97
																						B363650	STANDARD 6F		**2.820**	6F		VA05074728	
1	5	0.4	0.4	30																		B363651	111.50	112.78	**0.081**			VA05074728	1.28
2	1	0.8	1.6	30		1.0	q/chl	4			0.1											B363652	112.78	114.30	**0.126**			VA05074728	1.52
6	1	1.5	4.5	45	30	2.0	q/chl	5		0.1	2.0								1.0			B363653	114.30	115.82	**0.513**			VA05074728	1.52
2	1	0.5	0.8	45						1.0	2.0	0.1										B363654	115.82	117.35	**0.098**			VA05074728	1.53
4	1	1.0	2.2	30	45	0.2	q/chl	5			1.0											B363655	117.35	118.87	**0.107**			VA05074728	1.52
																						B363656	BLANK		**<0.005**			VA05074728	
5	1	0.4	1.8	45		1.0	q/chl	4			1.0											B363657	118.87	120.40	**0.294**			VA05074728	1.53
2	1	0.5	1.0	30							1.0		1.0									B363658	120.40	121.92	**0.151**			VA05074728	1.52
2	1	0.5	0.7	30		0.3	q/chl	4			1.0											B363659	121.92	123.44	**0.168**			VA05074728	1.52
3	1	0.8	1.5	45		1.0	chl	3			1.0		1.0									B363660	123.44	124.97	**1.860**			VA05074728	1.53
4	1	0.4	1.2	45	30	1.0	s/chl	3			2.0	1.0										B363661	124.97	126.49	**0.077**			VA05074728	1.52
4	"	0.4	1.2	45	30	1.0	s/chl	3			2.0	1.0										B363662	124.97	126.49	**0.077**	DUP		VA05074728	1.52
6	"	1.0	3.0	45	30	0.5	s/chl	3			2.0		1.0									B363663	126.49	128.02	**0.041**			VA05074728	1.53
3	1	1.0	1.7	5	10	0.2	q/chl	5			3.0											B363664	128.02	129.55	**0.177**			VA05074728	1.53
3	1	0.3	0.7	45		1.0	q/chl	3			2.0											B363665	129.55	131.06	**0.258**			VA05074728	1.51
4	1	0.5	1.5	45		1.5	chl	5			2.0		2.0									B363666	131.06	132.54	**0.111**			VA05074728	1.48
3	5	0.5	1.5	45							1.0	0.1	1.0																
9	1	2.0	7.6	45		2.0	s	4		1.0	4.0	0.1	1.0									B363667	132.54	134.11	**0.189**			VA05074728	1.57
4	1	1.0	3.0	45		1.0	s/chl	4		0.1	2.0											B363668	134.11	135.64	**0.085**			VA05074728	1.53
4	1	1.0	3.0	45		1.0	s/chl	4		0.1	2.0											B363669	134.11	135.64	**0.055**	PD/CA		VA05074728	1.53
																						B363670	STANDARD 5E		**1.490**	5E		VA05074728	
6	1	1.5	4.0	45	30	1.0	s/chl	4			5.0	1.0	1.0									B363671	135.64	137.16	**0.302**			VA05074728	1.52
1	3	0.3	0.3	45		1.0	chl	5																					
1	5	0.4	0.4	45		1.0	chl	4					1.0																
2	1	2.0	3.5	45							2.0	1.0	0.1									B363672	137.16	138.68	**0.296**			VA05074728	1.52
1	5	0.2	0.2	45		0.5	chl	4																					
4	1	1.2	2.5	45							1.0		1.0									B363673	138.68	140.21	**0.113**			VA05074728	1.53
3	1	1.0	2.0	45		1.0	chl	4		1.0	2.0	1.0	0.1									B363674	140.21	141.73	**0.188**			VA05074728	1.52
5	1	1.1	3.5	45	30	0.2	q	5			3.0	1.0	0.1									B363675	141.73	143.26	**0.063**			VA05074728	1.53
																						B363676	BLANK		**0.010**			VA05074728	
2	1	1.5	1.8	45							2.0		1.0									B363677	143.26	144.76	**0.045**			VA05074728	1.50
2	1	0.6	1.0	45							2.0		2.0									B363678	144.76	146.18	**0.077**			VA05074728	1.42
1	5	0.4	0.4	45		0.3	k	5			2.0		0.1																

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 7 of 12	
DRILL HOLE # : **DG05-300C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		147.83	156.32	GND: Grey GND that is more heavily fractured and broken up than the previous interval (124.97 - 147.83m); Long shallow (0-30°) fractures abundant with cb/s/chl and commonly pyrite; At 153.7m = 1cm felsic granitic (very fine grained) vein at 30° TCA; Slickenlines: at 150.65m, face at 45° with lines at 50° TCA.		2	2	3	2	
10		156.32	166.24	GND: Grey GND; GND still more heavily fractured than previous interval (147.83 - 156.32m) with a general size of 4x4x3cm; Locally more competent core up to 35cm in length; Locally very crumbly sand sized; Blocks commonly have sericite +/- chlorite alteration; Fracture faces mostly have calcite with a tinge of green (pale sericite), commonly with pyrite; Slickenlines: 165.65m, face to 45° and lines at 50° TCA; At 163.37m, face at 60° with lines at 65° TCA; At 165.85m, face at 30°, lines at 45°.		2	2			
10		166.24	168.46	GND: Intensely sericite altered =/- chlorite alteration; Extremely crumbly to completely altered core; Crumbly core contains remnant quartz veins as quartz eyes aligned; Disseminated pyrite throughout; Competent core has abundant carbonate throughout; Slickenlines at 168.43m with face at 5° and lines at 70° TCA.		5	2			
10		168.46	175.00	GND: Grey GND, competent; Quartz veins tend to have large-moderate sericite selvages; No real obvious alteration in interval.						
10		175.00	189.63	GND: Majority of GND has been argillic altered; Contacts between unaltered GND and argillic altered GND tends to be sharp at about 45-60° (vein parallel?); Unaltered intervals ~60m (4 of them); Sericite selvages occur along fractures with calcite and chlorite on fractures (up to 6cm); Common to see quartz veins at edge of sericite/chlorite fracture selvages; Slickenlines: At 178.2m, face at 45° with lines at 45° TCA; At 178.7m, frac at 20° with lines at 60°; At 184.7m, face at 10° with lines at 20° TCA; At 190.25m, face at 30° with lines at 60°.				4	1	

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 3 of 12
Selvages: 0 = No Alteration, 5 = Intense Alt'n; Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass	
Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite		
Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz		

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	2	0.3	0.6	45							2.0																		
7	1	1.0	3.0	45	30	0.3	k/s	5		1.0	5.0		0.1									B363679	146.18	147.83	0.119			VA05074728	1.65
1	3	0.3	0.3	45																									
2	5	0.3	0.6	45							2.0																		
3	1	0.3	0.8	45	30	0.2	q	5			2.0		2.0									B363680	147.83	149.35	0.066			VA05074728	1.52
2	1	1.5	1.8	60	30	2.0	s	5		2.0	1.0		2.0									B363681	149.35	150.88	0.076			VA05074728	1.53
2	1	1.5	1.8	60	30	2.0	s	5		2.0	1.0		2.0									B363682	149.35	150.88	0.144	DUP		VA05074728	1.53
4	1	1.0	3.0	60	45					1.0	1.0											B363683	150.88	152.40	0.102			VA05074728	1.52
1	3	0.2	0.2	30						0.1	0.1																		
0																						B363684	152.40	153.92	0.139			VA05074728	1.52
0																						B363685	153.92	155.45	0.224			VA05074728	1.53
4	1	0.6	2.0	45		3.0	s/cb			3.0	5.0	0.1	2.0									B363686	155.45	156.32	0.472			VA05074728	0.87
1	1	0.3	0.3	30																		B363687	156.32	157.62	0.098			VA05074728	1.30
0																						B363688	157.62	159.15	0.094			VA05074728	1.53
0																						B363689	157.62	159.15	0.086	PD/CA		VA05074728	1.53
																						B363690	STANDARD 6F		2.680	6F		VA05074728	-
4	1	0.6	1.8	45	30						4.0		2.0									B363691	159.15	160.02	0.177			VA05074728	0.87
7	1	0.6	3.0	45		0.3	cb/chl				1.0		1.0									B363692	160.02	161.54	0.067			VA05074728	1.52
0																						B363693	161.54	163.07	0.287			VA05074728	1.53
2	1	0.8	1.6	45						0.1												B363694	163.07	164.59	0.072			VA05074728	1.52
1	1	0.3	0.3	45							1.0		1.0									B363695	164.59	165.50	0.181			VA05074728	0.91
																						B363696	BLANK		0.009			VA05074728	
2	1	0.5	1.0	60									0.1									B363697	165.50	166.24	0.349			VA05074728	0.74
0																						B363698	166.24	167.61	0.299			VA05074728	1.37
7	1	1.6	6.0							5.0												B363699	167.61	168.46	5.460			VA05074728	0.85
6	1	1.0	2.6	45		5.0	s	3		2.0	3.0		2.0									B363700	168.46	169.90	0.209			VA05074728	1.44
3	1	0.6	1.5	45		1.0	q/s	4			2.0											B363701	169.90	170.69	0.435			VA05074728	0.79
3	1	0.6	1.5	45		1.0	q/s	4			2.0											B363702	169.90	170.69	0.121	DUP		VA05074728	0.79
3	1	1.0	2.2	45		11.0	s/cb	4			2.0		0.1									B363703	170.69	172.21	0.099			VA05074728	1.52
5	1	1.0	3.0	45	30	0.5	q/s	4			2.0		3.0									B363704	172.21	173.74	0.141			VA05074728	1.53
3	1	0.4	1.1	30	45						1.0											B363705	173.74	175.00	0.082			VA05074728	1.26
0																						B363706	175.00	176.23	0.286			VA05074728	1.23
0																						B363707	176.23	176.91	0.027			VA05074728	0.68
1	1	1.0	1.0	45							1.0		1.0									B363708	176.91	178.31	0.198			VA05074728	1.40
1	1	1.0	1.0	45							1.0		1.0									B363709	176.91	178.31	0.190	PD/CA		VA05074728	1.40
																						B363710	STANDARD 4D		0.457	4D		VA05074728	
1	1	0.5	0.5	30		3.0	s/q	3		1.0	2.0		2.0									B363711	178.31	179.83	0.443			VA05074728	1.52
2	6	0.2	0.4	45		0.4	q	5			25.0																		
2	1	1.0	1.6	45							1.0		1.0									B363712	179.83	181.36	0.089			VA05074728	1.53
1	1	0.5	0.5	45		0.3	q	5			4.0											B363713	181.36	182.88	2.110			VA05074728	1.52
6	1	1.5	3.0	45		0.3	q	5			2.0											B363714	182.88	184.40	0.089			VA05074728	1.52
1	1	0.3	0.3	45							1.0											B363715	184.40	185.33	0.150			VA05074728	0.93
																						B363716	BLANK		<0.006			VA05074728	
3	1	0.5	1.5	45							2.0											B363717	185.33	186.87	0.134			VA05074728	1.54
4	1	0.5	1.5	45	30	2.0	s/chl	4		1.0	2.0	0.1	2.0									B363718	186.87	188.27	0.145			VA05074728	1.40
3	1	0.2	0.6	45		0.2	q	4			2.0											B363719	188.27	189.63	1.255			VA05074728	1.36

DRILL LOG LEGEND P1	DATE: August 14-20th 2005	PAGE 4 of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		189.63	219.94	GND: GND appears to have various degrees of ser/chl/arg/carb alteration; Sericite alteration is dominant throughout; Carb and clay alteration tend to occur together where core is very crumbly; Clay altered core has disseminated f g py (1-2%) throughout and mm-scale veinlets; Disseminated pyrite occurs in dark-grey clay veins; Competent core goes through color change gradually (k-spar + ser = ser = ser + chl); K-spar alteration may be overprinted by sericite alteration (soft, non reactive creamy grains); Contacts with clay/carb altered core tends to be sharp; Q V at 194.3m has euhedral pyrite (up to 2x2.2mm); In highly clay/carb/sericite altered GND large Q V are broken up with abdnt euh-subhed py; At 207.26m core white wi hint of green, grey q.v's w/in, qtz blebs abndt or area of silicification (4x8cm), cb vning abundt, ends at 208.79m; Slickenlines: at 201.0m, face at 10° wi lines at 35°; At 207.66m = 45° wi lines at 85°; At 209.75m = 45° wi lines at 75°; At 212.32m = 30° wi lines at 85°; At 216.41m = 60° wi lines at 70° TCA.		5	3	3	2	
10		219.94	231.19	GND: Grey GND; Mod - highly broken up; Chl + cb on fracture faces; Local argillic alteration with lesser carb alteration; Medium grained aspy and po present on fracture faces as well as fine grained py; Very gradually core is becoming lighter in colour and softer (argillic alteration); Large 15cm quartz vein at end of interval with a sharp contact to next interval; Slickenlines: At 222.3m, face at 45° with lines at 80° TCA; At 224.5m, face at 5° with lines at 90°; At 228.1m face at 5° with lines at 90°; At 230.2m face at 30° with lines at 45° TCA.		1		1	1	

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 10 of 12
Selvages 0 = No Alteration 5 = Intense Alt'n	**Ox. State** 0 = No Oxidized Sulphides 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						% of VEIN & DISSEMINATED MATERIAL																										
						Selvages				Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
6	1	4.0	60.0	45		2.0	s/chl	3			1.0											B363720	189.63	190.66	**0.163**			VA05074728	1.03
8	1	0.8	3.0	45	60	7.0	q/chl	5														B363721	190.66	192.02	**0.153**			VA05074728	1.36
8	1	0.8	3.0	45	60	7.0	q/chl	5														B363722	190.66	192.02	**0.360**	DUP		VA05074728	1.36
6	1	4.0	9.0	45		4.0	5	5		1.0	3.0	0.1	2.0									B363723	192.02	193.55	**1.745**			VA05074728	1.53
2	1	9.0	10.0	45						10.0	1.0		5.0									B363724	193.55	195.07	**7.650**			VA05074728	1.52
4	1	2.0	3.5	60	45					5.0			2.0									B363725	195.07	196.60	**2.490**			VA05074728	1.53
1	6	0.5	0.5	80						95.0												B363726	196.60	198.12	**0.745**			VA05074728	1.52
5	1	1.0	2.5	80	45					1.0												B363727	198.12	199.64	**0.294**			VA05074728	1.52
1	1	1.0	1.0	45						1.0			1.0									B363728	199.64	201.17	**0.188**			VA05074728	1.53
1	4	0.4	0.4	35																										
1	1	1.0	1.0	45						1.0			1.0									B363729	199.64	201.17	**0.146**	PD/CA		VA05074728	1.53
1	4	0.4	0.4	35																										
																						B363730	STANDARD 1A		**0.991**	1A		VA05074728	
2	1	2.0	2.5	45																		B363731	201.17	202.58	**0.555**			VA05074728	1.41
4	1	1.0	3.0	45	30					2.0			0.1									B363732	202.58	203.65	**0.577**			VA05074728	1.07
3	1	5.0	8.0							25.0												B363733	203.65	205.17	**1.725**		Py only in one vein	VA05074728	1.52
5	1	1.2	4.5	45							2.0		1.0									B363734	205.17	206.48	**0.477**			VA05074728	1.31
3	1	2.0	6.0	45	30					1.0	1.0		1.0									B363735	206.48	207.26	**13.360**			VA05074728	0.78
																						B363736	BLANK		**0.011**			VA05074728	
4	1	1.0	2.5	45	60																	B363737	207.26	208.79	**0.454**			VA05074728	1.53
0																						B363738	208.79	210.10	**0.357**			VA05074728	1.31
0																						B363739	210.10	211.44	**0.124**			VA05074728	1.34
0																						B363740	211.44	212.50	**1.150**			VA05074728	1.06
2	1	0.5	1.0	60						0.1	0.1		0.1									B363741	212.50	213.60	**0.514**			VA05074728	1.10
2	1	0.5	1.0	60						0.1	0.1		0.1									B363742	212.50	213.60	**0.291**	DUP		VA05074728	1.10
1	6	0.5	0.5	80						50.0												B363743	213.60	214.30	**0.116**			VA05074737	0.70
0																						B363744	214.30	216.01	**0.521**			VA05074737	1.71
0																						B363745	216.01	217.21	**0.596**			VA05074737	1.20
4	1	1.0	4.0	60							1.0	0.1	1.0									B363746	217.21	218.67	**0.790**			VA05074737	1.46
2	6	1.0	1.3	70						60.0			5.0									B363747	218.67	219.94	**0.383**			VA05074737	1.27
1	1	1.0	1.0	60						10.0			2.0																
3	1	1.0	2.0	60		0.8	k	4			2.0		2.0									B363748	219.94	220.98	**0.430**			VA05074737	1.04
3	1	1.0	2.0	60		0.8	k	4			2.0		2.0									B363749	219.94	220.98	**0.382**	PD/CA		VA05074737	1.04
																						B363750	STANDARD 6F		**2.870**	6F		VA05074737	
1	1	0.3	0.3	80		0.4	q	4														B363751	220.98	222.50	**0.392**			VA05074737	1.52
1	2	0.3	0.3	70																										
7	1	3.5	7.0	70		0.3	k	5		1.0	2.0		2.0									B363752	222.50	224.03	**0.462**			VA05074737	1.53
1	6	0.3	0.3	70																										
3	1	0.5	1.2	65		1.0	k	5			2.0		2.0									B363753	224.03	225.55	**0.744**			VA05074737	1.52
1	2	0.5	0.5	70																										
1	1	1.0	1.0	60							2.0	0.1	1.0									B363754	225.55	227.08	**0.440**			VA05074737	1.53
1	3	1.0	1.0	60							2.0																			
2	3	1.0	1.5	60		1.0	q/s	3			5.0											B363755	227.08	228.60	**0.803**			VA05074737	1.52
1	4	0.3	0.3	60																										
																						B363756	BLANK		**<0.005**			VA05074737	
5	1	1.7	6.5	50							2.0		0.1									B363757	228.60	230.12	**1.220**			VA05074737	1.52
1	2	0.5	0.5	50						2.0																				

DRILL LOG LEGEND - P1	DATE: August 14-20th 2005	PAGE \\ of 12	
DRILL HOLE # : DG05-300C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.19	246.89	GND: GND gradually increasing intensity of argillic alteration down hole; Slight to moderation at top of interval to extreme at EOH; Carb alteration and fracturing prevalent throughout; Local sericite alteration associated with dark grey clay(?); Where core is most intensely altered, only clay and quartz eyes remain (213.84 - 246.89m), also fresh v f gr blebs of py disseminated throughout 1-2%; Pyrite veinlets/blebs common in increased argillic alteration; Quartz vein commonly displaced. Slickenlines: At 232.2m, face at 10° with lines at 75°; At 233.3m face at 10° with lines at 45°; At 236.1m face at 10° with lines at 45° TCA.		1		5	3	
				EOH						

094876

DRILL LOG LEGEND P2	Date: August 14-20th, 2005	PAGE 12 of 12
Selvages: 0 = No Alteration, 5 = Intense Alt'n; Ox. State: 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized	LOGGED BY: K Piepgrass	
Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite		
Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz		

VEINS						% of VEIN & DISSEMINATED MATERIAL																Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.3	0.3	60		0.3	q	4			20.0		5.0									B363758	230.12	230.85	**0.267**			VA05074737	0.73
2	1	15.0	20.0	45						1.0			0.1									B363759	230.85	231.19	**7.420**			VA05074737	0.34
0																						B363760	231.19	232.63	**8.820**			VA05074737	1.44
2	1	0.6	0.8	70		0.5	q	5			4.0											B363761	232.63	234.48	**0.357**			VA05074737	1.85
2	1	0.6	0.8	70		0.5	q	5			4.0											B363762	232.63	234.48	**0.190**	DUP		VA05074737	1.85
6	1	1.0	2.5	75							2.0		0.1									B363763	234.48	236.16	**0.817**			VA05074737	1.68
2	6	0.5	0.7	75							25.0																		
1	1	1.0	1.0	80							2.0											B363764	236.16	237.51	**0.356**			VA05074737	1.35
4	1	15.0	37.0	45	60						1.0											B363765	237.51	239.27	**1.645**			VA05074737	1.76
1	6	0.3	0.3	70						90.0																			
0																						B363766	239.27	240.79	**1.110**			VA05074737	1.52
0																						B363767	240.79	242.32	**1.060**			VA05074737	1.53
0																						B363768	242.32	243.84	**0.870**			VA05074737	1.52
0																						B363769	242.32	243.84	**0.956**	PD/CA		VA05074737	1.52
																						B363770	STANDARD 3C		**0.095**	3C		VA05074737	
0																						B363771	243.84	245.36	**1.945**			VA05074737	1.52
0																						B363772	245.36	246.89	**0.695**			VA05074737	1.53

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-301C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 994m

BEARING: 000 | DIP: -50°

DATE STARTED: 31-Jul-05 | DATE COMPLETED: 05-Aug-05

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459655 NORTHING: 7099185

COORD SYSTEM: NAD 83: EASTING: 459536 NORTHING: 7099370

NAD 27 (CORRECTED for historic grid): EASTING: 459625 NORTHING: 7099195

SECTION LINE(historic grid): 459625 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 3.65m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	3.65	Casing
3.65	308.02	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B381577 - B381600 and B364201 - B364316

Requisition #: MASP448STRGOL.05Q | Date Shipped: 19-Aug-05

Lab Record #: VA05072075 | Date Received: 25-Aug-05

Sample Sequence: 364317 - 364457

Requisition #: MASP448STRGOL.05Q | Date Shipped: 26-Aug-05

Lab Record #: VA05074726 | Date Received: 2-Sept-05

Duplicates:	381582; 364202; 364222; 364242; 364262; 364282; 364302; 364322; 364342; 364362; 364382; 364402; 364422; 364442
Preparation Duplicate/ Check Assay:	381589; 364209; 364229; 364249; 364269; 364289; 364309; 364329; 364349; 364369; 364389; 364409; 364429; 36449
Standards:	381590 (2B); 364210 (5E); 364230 (1A); 364250 (4D); 364270 (7G); 364290 (3C); 364310 (1A); 364330 (6F); 364350 (4D); 364370 (5E); 364390 (2B); 364410 (7G); 364430 (4D); 364450 ( )
Blanks:	381596; 364216; 364236; 364256; 364276; 364296; 364316; 364436; 364356; 364376; 364396; 364416; 364436; 364456

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
167.6	334.9	-51.4	000.9	001.9
213.4	335.3	-49.8	001.3	002.3
243.8	336.3	-47.8	002.3	003.3
304.8	336.3	-47.9	002.3	003.3

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

No surveys above 167.63m due to NQ casing

DRILL LOG LEGEND - P1	DATE: Aug 14 - 20, 2006	PAGE 1 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-3.65	0.00	3.65	Casing						
10	3.65-17.34	3.65	17.34	GND: 40% pervasively stained GND; Very broken up where competent, with longest core length of 19cm; Weathered to clay over 20% of section; This clay is pale whitish-yellow brown or bright orange-brown; Recovery is poor to excellent (0% - 87%); Generally corresponding to clay context (increased clay = reduced recovery); First 5 samples contain selvage-less 0.5cm quartz veins at ~60° TCA, as well as wide selvages (primarily oxidized) with no visible veinage; These selvages probably result from microfractures serving as channels for atmospheric and meteoric waters; From 12.19 - 17.34m is 90% stained pale brown, even through competent sections; Boundary between oxidized and unoxidized is clear but irregular, surrounding veinlets and veins.	3	0	0	1	1	
10		17.34	24.38	GND: 60% of section is oxidized and limonitic GND reduced to sandy/granular texture - fine to coarse. Colour is pale yellowish brown; Yellow due to oxidized carbonate (still effervesces weakly); Competent GND sections (up to 10cm long) are pervasively oxidized to pale brown, but with GND texture preserved; Fine grained, 2mm minerals (bt, feldspar) maximum diameter.	4	0	0	1	1	
10		24.38	35.05	GND: Intensely broken-up, crumbly GND; Sandy texture over 80% of section; All limonitic and ox'd; Competent core (up to 20cm long) is pale brown, ox'd with pervasive limonite; Texture preserved in only 10% of competent material rest is faulted such that the rock is aphanitic and has brecciated (angular) quartz along planar foliation at 50° (40-60°) TCA; Definitive fault material between 26.7 - 27.35m and from 32.0 - 33.0m in competent sections; Broken regularly at 70° TCA.	5	0	0	1	1	
10		35.05	48.45	GND highly weathered by closely-spaced veinlets of carbonate-rich limonitic material throughout matrix. Feldspars weathering to clay minerals. Broken-up crumbly; Veins less visible. Small veins of calcite produce carb-rich selvages/zones; Soft, opaque, dull grey, semi-metallic sulphide in quartz veins (chalcocite?) appears, <5% of vein, somewhat (~50%) weathered to chlorite/sericite; At 39.7m = quartz/k-spar vein contains increased hem (ox'd), hematite continues; Increasingly brecciated through section, last 3m contain no competent pieces larger than 10cm long; Texture is brecciated - GND chunks in crumbly clay/fine to coarse sand-size material matrix.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorolite	biotite	other		From	To					
2	1	2.0	2.5	60		0.0																B381577	3.65	4.57	**0.076**		2cm vein in pieces; No selvages seen	VA05072075	0.92
1	1	3.0	3.0			3.0	q/chl	3	3								0.1					B381578	4.57	6.10	**1.135**		Trace Chalcocite (?); Pieces of vein and selvage	VA05072075	1.53
1	1	0.5	0.5	55		0.0				0.0												B381579	6.10	7.62	**0.026**		Selvages seen but no vein.	VA05072075	1.52
				60	120	6.0	q/chl	2	5																			
4	2	0.5	1.6	0	50	1.0	q/k	2	4													B381580	7.62	9.14	**0.060**			VA05072075	1.52
1	1	0.4	0.4	70		0.0											3.0										Trace Chalcocite		
2	2	1.0	1.0	55		1.0	q/k	1	3													B381581	9.14	10.67	**0.046**			VA05072075	1.53
1	1	1.0	1.0	20						0.1																			
2	2	1.0	1.0	55		1.0	q/k	1	3													B381582	9.14	10.67	**0.037**	DUP		VA05072075	1.53
1	1	1.0	1.0	20						0.1																			
6	1	2.0	6.0	60		2.0	q/k	4	3	0.1							2.0					B381583	10.67	12.19	**0.048**			VA05072075	1.52
1	1	0.4	0.4	55													0.1					B381584	12.19	13.72	**0.055**		Trace moly (?)	VA05072075	1.53
																							13.72	15.24			No recovery; Clay seam	VA05072075	1.52
0																						B381585	15.24	16.76	**0.040**			VA05072075	1.52
0																						B381586	16.76	17.34	**0.036**			VA05072075	0.58
0																						B381587	17.34	18.29	**0.052**			VA05072075	0.95
0																						B381588	18.29	19.81	**0.038**			VA05072075	1.52
0																						B381589	18.29	19.81	**0.039**	PD/CA		VA05072075	1.52
																						B381590	STANDARD 2B		**2.880**	2B		VA05072075	
0																						B381591	19.81	21.34	**0.050**			VA05072075	1.53
1	1	0.6	0.6	50		1.0	q/k	3	2	0.0												B381592	21.34	22.86	**0.059**			VA05072075	1.52
0																						B381593	22.86	24.38	**0.068**			VA05072075	1.52
2	1	0.5	0.7	20		2.0	q/k	3	2	0.0												B381594	24.38	25.91	**0.087**			VA05072075	1.53
0																						B381595	25.91	27.43	**0.093**			VA05072075	1.52
																						B381596	BLANK		**<0.005**			VA05072075	
0																						B381597	27.43	28.96	**0.136**			VA05072075	1.53
0																						B381598	28.96	30.48	**0.091**			VA05072075	1.52
0																						B381599	30.48	32.00	**0.189**			VA05072075	1.52
0																						B381600	32.00	33.53	**0.310**			VA05072075	1.53
0																						B364201	33.53	35.05	**0.020**		New book	VA05072075	1.52
0																						B364202	33.53	35.05	**0.028**	DUP		VA05072075	1.52
0																						B364203	35.05	36.58	**0.031**			VA05072075	1.53
1	2	0.6	0.6	50		2.0	q/k	2	2													B364204	36.58	38.10	**0.044**			VA05072075	1.52
2	1	2.0	3.0	50		0.5	q/k/cb	2	2													B364205	38.10	39.62	**0.039**			VA05072075	1.52
2	2	1.0	1.5	60	10	0.5	cb/k	3	2								2.0												
3	2	1.0	2.0	50		1.0	cb/k	4	3													B364206	39.62	41.15	**0.111**			VA05072075	1.53
4	1	0.8	3.0	70	50	2.0	cb/q	3	3													B364207	41.15	42.67	**0.087**			VA05072075	1.52
1	1	1.0	1.0	70		1.0	q	1	5													B364208	42.67	44.20	**0.032**			VA05072075	1.53
1	1	1.0	1.0	70		1.0	q	1	5													B364209	42.67	44.20	**0.033**	PD/CA		VA05072075	1.53
																						B364210	STANDARD 5E		**1.490**	5E		VA05072075	
2	1	1.0	2.0	50		2.0	q	1	3													B364211	44.20	45.72	**0.046**		Oxidized hematite; brecciated quartz	VA05072075	1.52
2	3	1.5	2.5	60		5.0	cb	3	5																				

DRILL LOG LEGEND - P1	DATE: Aug 14 - 20, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-301C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		48.45	56.88	FAULT ZONE. GND texture reduced to 1mm-grain size; coherent core 50% of section, shows re-arranged, brecciated fine grained GND; Considerably weakened/weathered along veinlets of carb-rich limonite in irregular orientations approximately 5 veinlets/square cm.	4	1	1	2	2	
10		56.88	75.53	GND: Typical GND texture re-appears, with fewer, but still prevalent limonite coated veins, causing intense breakage. Selvages around limonite veinlets are visible here (again) - irregular in width, up to 2cm; Moderate slickenslides on fracture faces at 20° TCA; Biotite, limonite, feldspar; 15cm silicified zone at 70.6m, broken at 30°-60° TCA.	3	0	1	1	1	
10		75.53	76.76	GND/FLT: Small zone of extreme weathering and aphanitic texture; FAULT ZONE: Brecciated-gouge for 20cm from 76.40 - 76.6m; General trend of shear is at 40° TCA; Veins are in first 30cm of sample	4	2	1	2	2	
10		76.76	89.07	GND; similar to 35.05-48.45m: Limonitic veinlets through matrix, weathering feldspars; Zones of intense shear noted; At 82.1 - 82.5m = Gouge/brecciated quartz/GND; At 84.25 - 84.85m = Clay gouge (30cm) and brecciated GND - shear to 130° OR 50°, At 87.42m - 88.35m = 90% clay, 10% brecciated GND and quartz. Strong shear to 30° TCA; At 79.3m = small sulphide vein (oxidized pyrite and aspy) parallels 1cm quartz vein; At 74.2m is an angular, 2cm xenolith of basalt which may contain sulphides (black, semi-metallic). From 83.82m - 84.18m is a zone of relatively unaltered GND; Calcite and limonite concentrated into veins/veinlets (8) at 160° TCA. This interval of coherent core is followed by 60cm of clay gouge and brecciated rock, heavily oxidized (noted above as zone of intense shear). At 87.42m, a 93cm zone of intense shear contains 2 quartz veins, slightly brecciated and probably re-oriented into shear direction.	4	0	0	2	2	
10		89.07	97.54	GND: Gradational zone between heavily limonized rock (entire hole to here) and white clay mineral/carb-rich GND with preserved texture (med-grained GND); Slickenslides visible in sericite/carbonate on fractures at <20° TCA; Diss aspy ~1 % of GND.	2	1	1	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 4 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL:												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorditie	biotite	other		From	To					
							chl/q	1																					
1	3	1.0	1.0	80		6.0	cb	3	4													B364212	45.72	47.24	0.030			VA05072075	1.52
4	1	1.2	4.0	40	50	2.0	q/k	1	3													B364213	47.24	48.45	0.149			VA05072075	1.21
1	1	1.0	1.0	65																		B364214	48.45	49.39	0.026		Brecciated Quartz	VA05072075	0.94
1	1	0.6	0.6	60		0.5	q/cb	2	3													B364215	49.39	50.29	0.055			VA05072075	0.90
																						B364216	BLANK		<0.005			VA05072075	
0																						B364217	50.29	51.82	0.044			VA05072075	1.53
3	1	1.2	3.2	60		0.0				5.0							0.1	1.0				B364218	51.82	53.34	1.160		Trace moly	VA05072075	1.52
1	1	1.0	1.0	50																		B364219	53.34	54.86	0.079		Gradational Boundaries	VA05072075	1.52
3	4	2.0	4.0	160	145	0.0																B364220	54.86	56.39	0.083			VA05072075	1.53
2	1	1.0	2.0	50		4.0	q/cb	3	2	0.1								5.0											
2	1	1.0	2.0	50		4.0	q/cb	1	3	2.0								5.0				B364221	56.39	56.88	0.064			VA05072075	0.49
2	1	1.0	2.0	50		4.0	q/cb	1	3	2.0								5.0				B364222	56.39	56.88	0.062	DUP		VA05072075	0.49
3	1	1.0	3.0	65		0.5	q/cb	2	2	3.0							0.1	5.0				B364223	56.88	57.91	0.053		Trace moly	VA05072075	1.03
2	1	1.0	2.0	40	70	2.0	q/cb	1	3	2.0								5.0				B364224	57.91	59.44	0.099		~10% hem	VA05072075	1.53
5	1	1.0	5.0	50		0.0							4.0					3.0				B364225	59.44	60.96	0.234			VA05072075	1.52
3	1	2.2	4.5	50		4.0	q/k/cb	2	2													B364226	60.96	62.48	0.080			VA05072075	1.52
4	1	0.8	3.0	50	60	1.5	q/cb/k	3	1		0.1									3.0		B364227	62.48	64.01	0.117			VA05072075	1.53
2	1	1.5	2.0	2		1.0	q/k/cb	2	2													B364228	64.01	65.53	0.046			VA05072075	1.52
2	1	1.5	2.0	2		1.0	q/k/cb	2	2													B364229	64.01	65.53	0.057	PD/CA		VA05072075	1.52
																						B364230	STANDARD 1A		0.843	1A		VA05072075	
0																						B364231	65.53	67.06	0.056			VA05072075	1.53
2	1	1.0	2.0	50		1.0	q/k	3	3				2.0						4.0			B364232	67.06	68.58	0.082			VA05072075	1.52
1	1	2.0	2.0	5		1.0	q/cb	2	3	1.0			0.1					5.0				B364233	68.58	70.10	0.066			VA05072075	1.52
0																						B364234	70.10	71.63	0.035			VA05072075	1.53
2	1	1.0	1.5	60	35	1.0	q/cb	2	2	1.0					1.0			5.0				B364235	71.63	73.15	0.094			VA05072075	1.52
																						B364236	BLANK		<0.005			VA05072075	
2	1	0.6	1.2	30	60	2.0	q	2	4				1.0									B364237	73.15	74.68	0.111			VA05072075	1.53
1	1	1.0	1.0	50		2.0	q	2	4	0.1								5.0				B364238	74.68	75.53	0.166			VA05072075	0.85
1	6	0.4	0.4	50		1.0	q	3	2	40.0			20.0					4.0											
3	1	1.0	2.0	45	20	0.0				2.0					0.1			5.0				B364239	75.53	76.76	0.270			VA05072075	1.23
3	3	0.5	1.5	50		1.0	q/cb	2	3	5.0		0.1	0.1		2.0			3.0				B364240	76.76	77.72	0.207			VA05072075	0.96
2	1	1.0	2.0	50		0.0				0.1								5.0				B364241	77.72	79.25	0.067			VA05072075	1.53
2	1	1.0	2.0	50		0.0				0.1								5.0				B364242	77.72	79.25	0.098	DUP		VA05072075	1.53
5	1	1.0	4.0	50	70	1.0	q	3	2	1.0			5.0		1.0			5.0	4.0			B364243	79.25	80.77	0.088			VA05072075	1.52
1	6	0.3	0.3	60		0.5	q	4	0	30.0			20.0					5.0											
2	1	1.0	1.7	70		0.0				0.1			0.1					5.0				B364244	80.77	82.30	0.023			VA05072075	1.53
5	1	1.5	5.5	40	50	2.0	q/cb	3	3	3.0	1.0							5.0				B364245	82.30	83.82	0.086			VA05072075	1.52
2	1	2.0	3.0	70	45						6.0		3.0					1.0	3.0			B364246	83.82	85.34	0.114			VA05072075	1.52
1	4	0.3	0.3	160		0.0				0.0																			
3	1	1.5	3.0	60		1.0	q/cb	3	3	1.0			1.0		5.0			5.0				B364247	85.34	86.87	0.105			VA05072075	1.53
2	1	2.0	4.0	30	60	0.0				1.0								5.0				B364248	86.87	88.39	0.126		Brecciated quartz in shear zone	VA05072075	1.52
1	1	2.0	4.0	30	60	0.0				1.0								5.0				B364249	86.87	88.39	0.107	PD/CA		VA05072075	1.52
																						B364250	STANDARD 4D		0.336	4D		VA05072075	
2	1	0.3	0.6	45		2.0	q/cb	4	1	3.0			1.0	0.1				4.0	3.0			B364251	88.39	89.07	0.036		Grey quartz	VA05072075	0.68
3	1	1.0	3.0	30		1.0	q/cb	2	1						2.0			5.0				B364252	89.07	90.42	0.073			VA05072075	1.35
4	1	1.0	3.0	35	60	8.0	q/cb	2	2	1.0			8.0					5.0				B364253	90.42	91.44	0.094		Massive aspy	VA05072075	1.02
							cb/chl	3																					

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 5 of 16	
DRILL HOLE # : DG05-301C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		97.54	112.78	GND: Virtually no limonite staining left. GND is still soft and very broken up due to carbonate weathering. Competent core up to 24cm long in section. 80% is crumbly and less than 10cm long, not complete diameter due to <10° TCA pervasive fractures. Slickenslides in quartz/carb vein at 104.3m expressed in oxidized pyrite; Fracture plane at 10° TCA (rough surface). Sample from 104.51 - 105.16m contains many quartz veins, some crosscutting at 25° and 75° TCA; Veins at 75° appear later, po concentrated at intersection (1cm grain). Also veins at 50° TCA contain ~15% py and some cpy and py. Crosscutting veins again at 109.2m; Large (4cm) quartz vein with <1mm oxidized pyrite overprinted by small, 0.5cm wide quartz veins containing po concentrated at intersections with edge of larger vein.	1	1	1	3	4	
10		112.78	116.47	GND: Clay gouge zone with clayey oxidized sulphide lenses; Fabric/lenses are at 50-80° TCA. Brecciated GND and qtz (<2cm in diameter) make up ~30% of section. 70% of the grain sizes are 1-2mm and smaller. Sericitic and carbonate-rich; Color is pale beige to dark grey.	2	4	2	4	4	
10		116.47	128.02	GND: Coherent carb-rich core with 20% GND texture still present. Sulphide veins and veinlets pervade - ~5 per metre. Sometimes these veinlets are just partial, pinched out at lenses. No selvage info noted because alteration covers the entire section, as noted on this page.	2	3	1	3	4	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.0	3.0	50	60	2.0	q/cb	1	2				3.0					2.0				B364254	91.44	92.96	**0.054**		Massive aspy in massive black mineralization (py?)	VA05072075	1.52
1	4	0.2	0.2	70		2.0	q/cb	2	3																			
8	1	1.0	6.0	60		2.0	q/chl	2	0		2.0				0.1							B364255	92.96	94.49	**0.146**			VA05072075	1.53
																						B364256	BLANK		**<0.005**			VA05072075	
4	1	1.0	3.0	60		0.0					4.0				1.0							B364257	94.49	96.01	**0.028**			VA05072075	1.52
3	1	1.0	3.0	70		1.0	q	1	0		0.1		0.1		1.0							B364258	96.01	97.54	**0.573**			VA05072075	1.53
4	1	1.0	3.5	70		2.0	q	1	0		1.0		0.1			0.1						B364259	97.54	99.06	**0.080**			VA05072075	1.52
2	1	20.0	22.0	80		0.0				3.0	2.0		1.0					5.0				B364260	99.06	100.58	**0.049**		Vein contains ~20% calcite	VA05072075	1.52
2	3	9.0	11.0	40		6.0	cb/chl	3	1	3.0								4.0				B364261	100.58	102.11	**0.108**			VA05072075	1.53
3	1	1.0	3.0	60						3.0	2.0		2.0					4.0											
2	3	9.0	11.0	40		6.0	cb/chl	3	1	3.0								4.0				B364262	100.58	102.11	**0.083**	DUP		VA05072075	1.53
3	1	1.0	3.0	60						3.0	2.0		2.0					4.0											
5	1	1.0	5.0	60		1.0	q/chl	3	0	2.0	7.0	1.0	4.0					1.0				B364263	102.11	103.63	**0.068**		Pieces	VA05072075	1.52
1	3	2.0	2.0			6.0	cb/chl	3		1.0					0.1			5.0											
2	6	0.3	0.5	60		1.0	q/cb	3	1		####											B364264	103.63	104.51	**0.104**		Irregular Edges	VA05072075	0.88
3	1	2.0	4.0	60	80	1.0	q	2	0		5.0	1.0						4.0											
1	3	10.0	10.0			0.0				5.0	1.0							4.0											
9	1	1.5	7.5	25	75	2.0	q/cb	4	0		15.0	3.0	1.0									B364265	104.51	105.16	**0.157**			VA05072075	0.65
3	3	4.0	8.0	60		2.0	cb/chl	4	0	6.0			0.1		1.0			5.0				B364266	105.16	106.68	**0.209**		Aspy disseminated in selvage	VA05072075	1.52
1	6	1.0	1.0	60		8.0	cb/chl	5			80.0	4.0	1.0																
2	3	2.0	4.0	80		6.0	cb/chl	3	1	1.0								5.0				B364267	106.68	108.20	**0.311**		Irregular edges - angle?	VA05072075	1.52
3	1	3.0	5.0	60	45	8.0	cb/chl	3	0	5.0	5.0							5.0				B364268	108.20	109.73	**0.075**			VA05072075	1.53
1	3	0.4	0.4	65		2.0	cb/chl	3	0																				
3	1	3.0	5.0	60	45	8.0	cb/chl	3	0	5.0	5.0							5.0				B364269	108.20	109.73	**0.090**	PD/CA		VA05072075	1.53
1	3	0.4	0.4	65		2.0	cb/chl	3	0																				
																						B364270	STANDARD 7G		**4.320**	7G		VA05072075	
3	1	2.0	4.0	40	60	6.0	q	3	0	5.0					2.0			5.0				B364271	109.73	111.25	**0.093**		Massive aspy and py in separate veinlets	VA05072075	1.52
3	6	1.0	1.6	50	70	20.0	q/chl	4	1	50.0			60.0					3.0											
							s/cb	1																					
5	1	1.0	5.0	50		6.0	s/q/chl	4	1	5.0	2.0							5.0				B364272	111.25	112.78	**0.073**			VA05072075	1.53
2	3	0.8	1.3	50		4.0	q/chl	4	0	10.0								5.0									Oxidized py clay at margins of vein		
							cb																						
1	1	1.5	1.5	55						5.0								5.0				B364273	112.78	114.30	**0.319**			VA05072075	1.52
3	6	25.0	60.0	40						100.0								5.0									Clay gouge with py		
3	6	4.0	10.0	75	45					100.0								5.0				B364274	114.30	115.82	**0.312**			VA05072075	1.52
1	6	1.0	1.0	75						100.0												B364275	115.82	116.47	**0.067**			VA05072075	0.65
																						B364276	BLANK		**<0.005**			VA05072075	
3	1	2.0	4.0	55						10.0								4.0				B364277	116.47	117.35	**0.359**			VA05072075	0.88
3	6	1.0	2.0	70	80					100.0								5.0											
5	1	9.0	19.0	45						8.0			5.0					4.0				B364278	117.35	118.87	**1.890**			VA05072075	1.52
4	6	4.0	8.5	45	80					100.0								3.0											
6	6	0.2	1.0	60	50					100.0								5.0				B364279	118.87	119.62	**0.369**			VA05072075	0.75
1	1	0.6	0.6	25						2.0								5.0											
1	1	5.0	5.0	45						15.0								4.0				B364280	119.62	120.40	**0.709**			VA05072075	0.78
3	6	0.5	1.1		25					10.0								5.0				B364281	120.40	121.92	**0.246**			VA05072075	1.52
4	1	1.5	3.0	35	60					5.0	10.0							3.0											
3	6	0.5	1.1		25					10.0								5.0				B364282	120.40	121.92	**0.444**	DUP		VA05072075	1.52

DRILL LOG LEGEND - P1	DATE: Aug 14 - 20, 2005	PAGE 7 of 16	
DRILL HOLE # : DG05-301C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		128.02	140.11	GND: Beginning of visible selvages around qtz/sulphide veins, so 40% of section is unaltered. Veinlets of oxidized sulphides are common, only veins >2mm are recorded on second page, but veinlets are ~20/metre. Sulphide vein at 138.15m is branching into surrounding rock and pyrite (60% ox'd) appears disseminated into irregular veinlets for 20cm surrounding vein. Sheared-out GND with carb and sulphide-rich clays from 139.05 - 139.60m.						
10		140.11	144.78	GND: In addition to selvages surrounding qtz and sulphide veins, separated by unaltered GND: This section also contains zones of carbonate-rich clay gouge (2): from 140.2 - 141.22m and 143.56 - 143.8m. In these zones GND texture is 'smeared' out into a trend at 10-35° TCA. Slickenslides (minor) noted on low angle fracture faces (rough).	1	2	2	2	3	
10		144.78	155.44	GND: 80% unaltered GND. Competent core with excellent recovery. Selvages visible on infrequent qtz,carb and qtz/carb veins. One large qtz vein from 149.77m to 150.60m contains small chunks of altered GND; sericitic alteration at margins. Slickensides (minor) in calcite on rough, low-angle fracture faces. Change from HQ to NQ at 151.33m; Crumbly carb-infused section from 154.0m to 155.3m (last sample).	0	2	1	0	2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
4	1	1.5	3.0	35	60					5.0	10.0							3.0											
4	1	1.5	4.0	50						20.0								2.0				B364283	121.92	123.44	**0.316**			VA05072075	1.52
1	6	1.0	1.0	45	65					100.0								5.0											
5	1	3.0	6.0	35	65					10.0	0.1							4.0				B364284	123.44	124.97	**0.363**			VA05072075	1.53
3	6	0.2	0.6	45	35					60.0								5.0											
2	1	0.5	1.0	70						5.0	0.1							5.0				B364285	124.97	126.49	**0.333**			VA05072075	1.52
3	6	0.5	0.9	30	160					60.0								5.0											
1	1	3.0	3.0	35						10.0								3.0				B364286	126.49	128.02	**0.242**			VA05072075	1.53
5	6	0.3	1.5							100.0								5.0											
8	1	2.0	9.0	40	70						5.0							2.0				B364287	128.02	129.54	**0.297**			VA05072075	1.52
5	1	3.0	10.0	30	70	2.0	q/cb	3	0		5.0	0.1										B364288	129.54	131.06	**0.517**			VA05072075	1.52
1	3	7.0	7.0	30		0.0				0.1								5.0											
5	1	3.0	10.0	30	70	2.0	q/cb	3	0		5.0	0.1										B364289	129.54	131.06	**0.496**	PD/CA		VA05072075	1.52
1	3	7.0	7.0	30		0.0				0.1								5.0											
																						B364290	STANDARD 3C		**0.092**	3C		VA05072075	
2	1	2.0	3.0	55							2.0											B364291	131.06	132.59	**0.893**			VA05072075	1.53
1	3	1.0	1.0	40						10.0	2.0							5.0											
3	1	3.0	5.0	70-		8.0	cb/chl	4	1	10.0	20.0							4.0				B364292	132.59	133.47	**1.320**			VA05072075	0.88
4	6	0.4	0.9	65	40	10.0	cb/chl	5	1	80.0								5.0											
3	1	0.6	1.2	60		20.0	cb/chl	5	1													B364293	133.47	134.11	**0.099**			VA05072075	0.64
3	1	1.5	4.0	40	60					5.0	3.0							1.0				B364294	134.11	134.89	**1.180**			VA05072075	0.78
2	6	1.0	1.3	60						60.0								5.0											
5	1	2	3.5	60.0		8	cb/chl	4	1	5								5.0				B364295	134.89	135.64	**1.575**			VA05072075	0.75
2	6	0.3	0.6	60		12.0	cb/chl	5	1	80.0								3.0											
																						B364296	BLANK		**<0.005**			VA05072075	
3	1	1.5	3.0	60		30.0	cb/chl	4	1	2.0	2.0							5.0				B364297	135.64	136.41	**0.327**			VA05072075	0.77
2	4	2.0	3.0	30	60	30.0	cb/chl	5	1	4.0								5.0											
4	1	0.5	2.0	40	90	1.0	q	3	0		5.0											B364298	136.41	137.16	**0.029**			VA05072075	0.75
3	4	0.3	0.9	70	35	20.0	cb/chl	3																					
2	4	1.0	1.2	50	70	30.0	cb/chl	5	0	0.0												B364299	137.16	137.93	**0.073**			VA05072075	0.77
2	6	1.0	1.0	790		20.0	cb/chl	5	0	90.0								5.0											
5	1	1.0	3.0	30		20.0	cb/chl	4	1	5.0	0.1	0.1	0.1					2.0				B364300	137.93	138.68	**0.937**			VA05072075	0.75
2	6	3.0	3.3	30		25.0	cb/chl	5	3	100.0								3.0											
6	1	1.0	5.0	70	40	15.0	q.cb	4	0		10.0											B364301	138.68	140.11	**1.315**			VA05072075	1.43
6	1	1.0	5.0	70	40	15.0	q.cb	4	0		10.0											B364302	138.68	140.11	**3.330**	DUP		VA05072075	1.43
4	6	0.4	1.0	70		10.0	cb/chl	5	1	100.0								5.0				B364303	140.11	141.19	**0.259**			VA05072075	1.08
2	6	1.0	2.0	35		20.0	cb/chl	4	2	100.0																			
							chl	1																					
4	1	1.0	4.0	50	100	0.0																B364304	141.19	141.73	**0.739**			VA05072075	0.54
1	4	0.5	0.5	30		0.0																							
4	1	1.0	4.0	50		2.0	q/cb	3	0	10.0												B364305	141.73	143.26	**0.296**			VA05072075	1.53
3	1	1.0	2.5	40	100	6.0	q/chl	3	1		0.1											B364306	143.26	144.78	**0.146**			VA05072075	1.52
3	4	0.3	0.9	40		3.0	q/cb	3	1	20.0								4.0											
3	3	0.5	1.5	60	30	24.0	cb/chl	3		20.0	2.0						3.0	5.0				B364307	144.78	146.30	**0.084**		Moly in selvages	VA05072075	1.52
3	1	1.0	2.5	50		8.0	q/chl	3	0	1.0	3.0	5.0										B364308	146.30	147.83	**1.705**			VA05072075	1.53
3	4	0.3	0.8	50		10.0	cb/chl	4	1	40.0								5.0											
3	1	1.0	2.5	50		8.0	q/chl	3	0	1.0	3.0	5.0										B364309	146.30	147.83	**1.775**	PD/CA		VA05072075	1.53
3	4	0.3	0.8	50		10.0	cb/chl	4	1	40.0								5.0											
																						B364310	STANDARD 1A		**0.810**	1A		VA05072075	
2	1	1.0	2.0	60		2.0	q/chl	2	1		10.0											B364311	147.83	149.35	**1.415**			VA05072075	1.52
2	1	1.0	2.0	60		2.0	q/chl	4	0																				
3	1	83.0	85.0	45		4.0	q/a	5		0.1	0.1		0.1									B364312	149.35	150.88	**0.134**			VA05072075	1.53
							cb/chl	2	1																				
2	1	2.0	4.0	80		10.0	q	3		4.0							0.1	1.0				B364313	150.88	152.41	**0.091**			VA05072075	1.53
2	1	0.5	1.0	75	15	0.5	q/cb	3	0													B364314	152.41	155.44	**0.065**		Error; 3m sample	VA05072075	3.03
1	3	1.0	1.0	45		3.0	q/chl	2	0																				

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 9 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		155.44	162.36	GND: Predominantly (90%) altered GND with chlorite and carbonate, minor sericite. Zone of many sulphide veinlets/few <1cm veins, approx 3 per m. Competent core, but softened to clay-rich in selvages surrounding sulphide veins. Oxidation of pyrite and carbonate.	1	2	3	1	2	
10		162.36	165.84	Larger qtz veinlets within still-competent GND. Sulphide veins continue with clay'd, oxidized pyrite, to a maximum alteration selvage of 50cm. Still, due to decreased number of veins and veinlets, more unaltered GND is present (50%).	1	2	2	0	1	
10		165.84	169.71	Carbonate-infused GND. Crumbly and soft, makes veins/veinlets difficult to see.	1	1	1	3	3	
10		169.71	181.50	GND: Unaltered, with quartz veins with small selvages; 60% of these veins have straight edges and clear selvages; 40% have gradational/irregular boundaries with little to no selvages.	0	1	1	0	1	
10		181.50	184.54	GND: 95% powdery/crumbly carb-infused GND.	0	1	0	2	4	
10		184.54	191.07	GND: Coherent core, but highly altered with chlorite, sericite and carb; Carb appears in veins and veinlets, generally at 50° TCA; as well as in ~2mm grains in selvages (alt'd feldspar); GND here appears finer-grained and sheared toward the end of the section. Slickenslides on fracture faces at moderate angles TCA (20-50°). Perfect cubic pyrite (1.2mm) at 188.66m.	1	2	3	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	6	0.6	1.1	45		40.0	q/cb/chl	4	1	100.0								5.0				B364315	155.44	156.97	0.672			VA05072075	1.53
1	1	1.5	1.5	50		1.0	q	2		2.0			0.1					3.0											
																						B364316	BLANK		<0.005			VA05072075	
3	1	1.0	2.0	70		5.0	q/chl	4	1	2.0	0.1		4.0					3.0				B364317	156.97	158.50	0.286			VA05074726	1.53
3	6	0.3	0.9	60		12.0	q/cb/chl	5	1	100.0								4.0											
2	1	1.5	2.0	70		2.0	cb/s	3	1		10.0	0.1										B364318	158.50	160.02	0.156		Clay selvage	VA05074726	1.52
2	6	0.3	0.6	55		40.0	cb/chl	5	1	100.0								4.0											
2	1	1.0	2.0	50		2.0	q/cb/chl	3	0	5.0	5.0							4.0				B364319	160.02	161.55	0.085		Oxidized py, not po	VA05074726	1.53
1	3	1.0	1.0	80		10.0	cb/chl	5	0	0.0																			
1	6	1.0	1.0	70		50.0	cb/chl	5	0	100.0								5.0											
2	1	1.0	2.0	70	80	6.0	cb/chl	3			5.0							1.0				B364320	161.55	162.36	0.808		20% clay	VA05074726	0.81
3	6	0.5	1.5	80	35	40.0	q/s	3	1	100.0								5.0											
							cb/chl	2																					
1	1	1.5	1.5	50		6.0	q/chl	3			4.0	1.0										B364321	162.36	163.07	0.145			VA05074726	0.71
1	1	1.5	1.5	50		6.0	q/chl	3			4.0	1.0										B364322	162.36	163.07	0.144	DUP		VA05074726	0.71
1	3	0.8	0.8	45		4.0	q/cb/chl	3	0		20.0											B364323	163.07	164.60	0.293		Oxidized calcite	VA05074726	1.53
4	1	3.5	8.5	60		16.0	cb/chl	3	1	8.0								2.0											
1	6	0.3	0.3	50		12.0	cb/s	4	1	100.0								4.0											
1	1	1.0	1.0	50		8.0	q/cb/chl	3	0	10.0								1.0				B364324	164.60	165.84	1.325			VA05074726	1.24
1	3	1.0	1.0	155		10.0	q/cb/s	4	1	8.0								5.0											
0																						B364325	165.84	166.75	0.428			VA05074726	0.91
2	1	1.5	3.0	70		2.0	q/cb	3	0		5.0							4.0				B364326	166.75	168.06	0.584		Pale po	VA05074726	1.31
2	1	0.5	1.0	50	35	1.0	q/cb	3			2.0											B364327	168.06	169.16	0.168		Pyrite concentrated at edges	VA05074726	1.10
1	4	0.5	0.5	30		0.4	cb/chl	1	0	5.0								5.0											
2	1	1.0	2.0	50		4.0	q/cb	3	0		0.1							5.0				B364328	169.16	169.71	0.201			VA05074726	0.55
2	1	1.0	2.0	50		4.0	q/cb	3	0		0.1							5.0				B364329	169.16	169.71	0.195	PD/CA		VA05074726	0.55
																						B364330	STANDARD 6F		2.62	6F		VA05074726	
3	1	1.0	3.0	80	50	2.0	q/chl	1	0		20.0	1.0	2.0									B364331	169.71	170.68	0.23			VA05074726	0.97
4	1	1.5	4.0	55		1.0	q/chl	3		3.0			0.1					5.0				B364332	170.68	172.21	0.102			VA05074726	1.53
2	3	1.0	2.0	50		6.0	q/cb	3	1	10.0	0.1																		
3	1	6.0	8.0	50	70	10.0	q/cb/chl	3	0	4.0	20.0											B364333	172.21	173.73	1.685			VA05074726	1.52
2	6	0.8	1.3	40		3.0	q/cb	4	1	20.0	50.0							0.0											
4	1	1.5	35.0	50	60	1.0	q	3			2.0											B364334	173.73	175.26	0.056			VA05074726	1.53
3	1	1.2	2.0	50		2.0	q	3			2.0							2.0				B364335	175.26	176.20	0.297			VA05074726	0.94
																						B364336	BLANK		<0.005			VA05074726	
3	1	1.0	2.0	80	50	3.0	q/cb/s	3	0	0.1	3.0							1.0				B364337	176.20	177.12	0.019			VA05074726	0.92
4	1	2.0	4.5	50		3.0	q/cb/s	3	0		1.0	0.1										B364338	177.12	178.44	0.212			VA05074726	1.32
1	6	1.0	1.0	65		6.0	q/cb/s	5	0		60.0							1.0											
4	1	1.0	3.0	70		4.0	q/cb/s	5			5.0											B364339	178.44	179.98	0.405			VA05074726	1.54
3	1	2.5	5.5	50	35	2.0	q/cb/s	4			2.0							1.0				B364340	179.98	181.50	0.345			VA05074726	1.52
2	6	0.4	0.8	50		15.0	cb/chl	5		60.0								5.0											
1	1	1.0	1.0	55		2.0	q/cb/s	2	1		0.1											B364341	181.50	183.02	0.429			VA05074726	1.52
2	6	0.5	1.0	15		4.0	cb/chl	3		80.0								5.0											
1	1	1.0	1.0	55		2.0	q/cb/s	2	1		0.1											B364342	181.50	183.02	0.692	DUP		VA05074726	1.52
2	6	0.5	1.0	15		4.0	cb/chl	3		80.0								5.0											
3	1	1.5	4.5	60		2.0	q/cb/s	3	1	0.1								5.0				B364343	183.02	184.54	1.155			VA05074726	1.52
4	1	1.5	3.3	50		6.0	q/s	3	0	0.1			0.1					5.0				B364344	184.54	185.84	1.11			VA05074726	1.30
3	6	0.5	1.4	35		30.0	cb/chl	5	1	90.0				0.1															
1	1	1.0	1.0	60		3.0	q/cb/s	2	0		4.0							1.0				B364345	185.84	186.43	0.275			VA05074726	0.59
5	1	0.8	2.8	40	60	2.0	q/cb/s	4	0							0.1						B364346	186.43	187.45	0.957			VA05074726	1.02
3	6	1.0	2.5	40		40.0	cb/chl/s	5			80.0							3.0											
4	1	1.2	4.0	40	55	4.0	q/s/chl/cb	4	1	15.0	5.0							1.0				B364347	187.45	188.67	0.16			VA05074726	1.22
1	3	2.0	2.0	55		10.0	chl/cb	4	0	1.0								5.0											
1	6	1.0	1.0	60		6.0	q	2	0	100.0								3.0											
2	1	1.0	2.0	15						0.1								5.0				B364348	188.67	189.88	0.129			VA05074726	1.21
2	1	1.0	2.0	15						0.1								5.0				B364349	188.67	189.88	0.126	PD/CA		VA05074726	1.21
																						B364350	STANDARD 4D		0.42	4D		VA05074726	

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 11 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		191.07	196.23	GND: Unaltered GND with a few quartz veins and sulphide veinlets; Pyrite seen on face at 90° TCA, in slickenslides. Some are straight, while on the same face, slickens in py are curved.		1	1		1	
10		196.23	213.35	GND: Return of frequent quartz, qtz/carb and sulphide veins/veinlets, with wide selvages. Section is ~40% unaltered GND. Slickensides on margins of quartz vein at 90° TCA at 196.23m, in biotite, chlorite and s. From ~203.0m to 203.5m, alteration (chl,cb) appears to be confined between 2 quartz veins. This is where carb veins are concentrated as well. Two Carb veins (0.5cm and 1cm) between 212.24 and 212.35m contain vg in rounded 2-3mm form. This zone - 211.84 - 213.0m - is also a shear zone. Strong slickensides on sulphide covered fracture at 10° TCA in calcite and sericite. Adjacent to this face is an obviously sheared qtz vein with indication of sinistral movement along this 10° face. Slickensides are at 60° TCA.		2	3		2	
10		213.35	231.12	GND: 80% unaltered GND; widest selvage is 80cm and is associated with increased mineralization (pyrite veins). Qtz veins with low mineralization have only small qtz/chl/cb selvages (<3cm); Slickensides with py at 229.45m on fracture face at 20° TCA (similar to at 211 - 213m).						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2005

LOGGED BY: M. Stone

PAGE 12 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL																			
										Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	9.0	9.0	40						2.0	0.1		2.0					1.0				B364351	189.88	191.07	**2.2**			VA05074726	1.19
4	1	2.0	5.0	40	60	2.0	q/cb	2	0		3.0	0.1										B364352	191.07	192.31	**0.237**			VA05074726	1.24
3	1	1.3	2.7	50	65	1.0	q/cb	2			0.1							3.0				B364353	192.31	193.55	**0.101**			VA05074726	1.24
1	3	0.4	0.4	40		2.0	q/cb	3			4.0	1.0																	
4	1	2.0	4.0	50	90	1.0	q/chl	3	0	15.0	10.0							1.0				B364354	193.55	195.08	**0.312**			VA05074726	1.53
6	1	2.0	7.0	65	50	20.0	cb/chl	5	0	10.0												B364355	195.08	196.23	**0.369**			VA05074726	1.15
																						B364356	BLANK		**<0.005**			VA05074726	
5	1	2.0	5.0	40	90	40.0	cb/chl	4	1	10.0	8.0							3.0				B364357	196.23	197.75	**0.653**			VA05074726	1.52
2	6	0.4	0.7	50	30	10.0	cb/q	4																					
3	1	1.4	3.0	20	45	15.0	q/chl	4	1	0.1	0.1							3.0				B364358	197.75	199.28	**0.168**			VA05074726	1.53
3	4	0.7	1.2	40	55	10.0	q/s	4	1																				
4	1	1.5	3.0	35		18.0	q/cb/chl	5	1		2.0							3.0				B364359	199.28	200.80	**8.88**			VA05074726	1.52
3	6	1.0	3.0	60	40	20.0	cb/chl	5	1	100.0								4.0											
1	4	0.8	0.8	40		10.0	q/cb/s	5	1																				
2	1	1.0	2.0	45		1.0	q	3	0	0.1												B364360	200.80	201.45	**0.162**			VA05074726	0.65
2	3	3.0	3.3	35		9.0	q/chl	5		2.0								5.0											
4	1	1.2	4.0	35	55	6.0	q/chl	4							0.1			4.0				B364361	201.45	202.69	**0.202**			VA05074726	1.24
4	1	1.2	4.0	35	55	6.0	q/chl	4							0.1			4.0				B364362	201.45	202.69	**0.198**	DUP		VA05074726	1.24
4	1	3.0	6.0	50		0.0																B364363	202.69	204.21	**0.29**			VA05074726	1.52
3	3	1.0	3.0	80	45	50.0	q/cb/chl	5	1	0.1								5.0											
4	1	2.5	5.8	35	60	1.0	q	1			0.1							2.0				B364364	204.21	205.74	**0.107**			VA05074726	1.53
2	3	0.9	1.3	55	70	10.0	q/cb/chl	5	0	60.0								2.0											
4	1	2.0	5.0	30	50	20.0	q/cb/chl	5	1		12.0											B364365	205.74	207.27	**0.468**			VA05074726	1.53
5	1	4.5	8.0	35	45	30.0	cb/chl	4		10.0						0.1		1.0				B364366	207.27	208.79	**0.652**		Trace VG	VA05074726	1.52
3	6	0.5	1.3	25		60.0	cb	4		100.0								4.0											
							chl	3																					
2	1	1.5	2.2	60		18.0	cb/chl	3		13.0						0.1		1.0				B364367	208.79	210.32	**0.316**		Trace VG	VA05074726	1.53
3	4	2.0	2.8	30	50	50.0	cb/chl	4																					
4	1	1.0	4.0	40	60					0.1	0.1		0.1			0.1	0.1		5.0			B364368	210.32	211.84	**0.471**		Trace VG, Moly	VA05074726	1.52
1	4	0.5	0.5	60																									
4	1	1.0	4.0	40	60					0.1	0.1		0.1			0.1	0.1		5.0			B364369	210.32	211.84	**0.476**	PD/CA		VA05074726	1.52
1	4	0.5	0.5	60																									
																						B364370	STANDARD 5E		**1.265**	5E		VA05074726	
3	1	1.2	3.2	45		24.0	cb/chl	4	1		3.0											B364371	211.84	212.54	**0.386**			VA05074726	0.70
2	4	1.0	1.5	80		40.0	cb/chl	4								2.0	0.1												
1	1	5.0	5.0	50		38.0	chl/cb	4	1	40.0						2.0		3.0				B364372	212.54	213.35	**0.371**			VA05074726	0.81
4	1	1.0	2.2	40		1.0	q/cb	4	0	2.0	5.0											B364373	213.35	214.88	**0.168**			VA05074726	1.53
5	1	0.5	2.1	40	130	1.0	q/cb	4	0		4.0	1.0										B364374	214.88	216.41	**0.221**			VA05074726	1.53
1	6	0.6	0.6	37		0.0				80.0								5.0											
1	1	0.4	0.4	65	0					0.0												B364375	216.41	217.93	**0.075**			VA05074726	1.52
																						B364376	BLANK		**<0.005**			VA05074726	
3	1	0.5	1.5	45	65	1.0	q	3	0	0.1	2.0											B364377	217.93	219.45	**0.614**			VA05074726	1.52
6	1	0.5	3.0	50		2.0	q	2	0		1.0		1.0						4.0			B364378	219.45	220.98	**0.361**			VA05074726	1.53
5	1	4.0	7.3	60		2.0	q/cb	4	0	4.0								1.0				B364379	220.98	222.51	**2.88**			VA05074726	1.53
2	6	0.5	1.0	60		80.0	cb/chl	4	1	100.0								0.0				B364380	222.51	224.03	**0.468**			VA05074726	1.52
5	1	1.0	4.0	50	60	2.0	q/cb	3			0.1				0.1							B364381	224.03	225.56	**1.32**			VA05074726	1.53
5	1	1.0	4.0	50	60	2.0	q/cb	3			0.1				0.1							B364382	224.03	225.56	**0.666**	DUP		VA05074726	1.53
5	1	1.0	5.0	40	55	2.0	q/chl	2	0		8.0											B364383	225.56	227.08	**1.015**			VA05074726	1.52
1	6	0.3	0.3	50		15.0	cb/chl	4		100.0								4.0											
2	1	1.0	2.0	50		2.0	q/chl	2	0		3.0											B364384	227.08	228.61	**0.39**			VA05074726	1.53
3	3	1.0	3.0	60	50	4.0	q/chl	3			10.0		0.1					3.0											
4	1	1.0	3.0	20	60	1.0	q/cb	4			8.0											B364385	228.61	230.12	**0.309**			VA05074726	1.51
5	1	1.0	4.0	40	60	1.0	q/cb	3			5.0											B364386	230.12	231.12	**0.611**			VA05074726	1.00

DRILL LOG LEGEND P1	DATE: Aug 14 - 20, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-301C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		231.12	239.27	GND: Medium grained, with varying degrees of chl, cb, s and q alteration in selvages and along shear planes; These shear planes are at ~0-10° TCA and show an abrupt change from 'clean' GND to carb-infused or chl/cb alt'd GND; Also have slickensides in sericite and clay minerals. This is between 236.5 and 237.9m. Minor slickensides continue to end of section. Interesting note: lower (deeper) selvage around a vein is larger than the upper (shallower) selvage, due to gravity.	1	2	3	1	2	
10		239.27	281.94	GND: Unaltered GND with sheeted quartz veins. Alteration restricted to a few <1m zones, noted below. Slickenslides throughout section on 0-45° fracture faces (rough to smooth). Between 255m and 261m a weak foliation develops in GND, at 120° TCA. Also, rock appears somewhat coarser-grained here, with an increase in 5mm carbonat, 5mm feldspars, 1cm quartz and 3mm black biotite. Length-wise to core, 4cm wide oxidized carb and iron section from 259.2 to 260.6m. At 264.85 - 266.02m, rock is solid selvage around 2 carb veins (3cm and 2cm wide). Their selvages are dominated by chlorite, but are still competent core. Scratchable with a nail. Carb is fine-grained in these selvages; overall color is yellowish deep green. At 267.2 - 267.37m is a dyke of mafic, aphanitic silicified rock. Coarse GND surrounds it on either side, with extra carbonate as well, for ~8cm on either side. Appears like lamprophyre dike. Intersects GND at ~50° TCA. From 276.5 - 276.95m another solid green selvage surrounding 2 quartz veins close together. Again, from 279.05 - 280.2m is a highly chloritized and moderately carbonitized zone. Sulphides disseminated t	1		1		2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	5.5	10.0	60		11.0	chl/q/s	4	1	15.0	5.0		0.1					2.0				B364387	231.12	232.32	**1.55**		Aspy at margins; Py and po in lenses in qtz	VA05074726	1.20
4	1	1.3	4.5	60		1.0	q	3	0		3.0		0.1		0.1				4.0			B364388	232.32	233.17	**0.291**			VA05074726	0.85
4	1	1.3	4.5	60		1.0	q	3	0		3.0		0.1		0.1				4.0			B364389	232.32	233.17	**0.21**	PD/CA		VA05074726	0.85
																						B364390	STANDARD 2B		**NSS**	2B		VA05074726	
6	1	1.1	4.5	40	60	8.0	q/chl	3	0	0.1	4.0		0.1									B364391	233.17	234.69	**0.748**			VA05074726	1.52
1	3	0.5	0.5	55		10.0	q/chl	4		4.0	2.0		0.1						4.0								Aspy in selvage		
5	1	1.0	5.0	60		8.0	q/chl	3			1.0		0.1									B364392	234.69	236.22	**1.01**			VA05074726	1.53
1	1	9.5	9.5	45		20.0	q/cb/chl	4	1	8.0				0.1								B364393	236.22	237.44	**10.2**			VA05074726	1.22
3	1	1.2	3.0	50	30	15.0	q/chl	4	2	5.0	2.0							5.0				B364394	237.44	238.03	**0.969**		Ox'd py in selvage	VA05074726	0.59
3	1	2.0	4.0	45		120.0	q/cb/chl	5	1	0.1								5.0				B364395	238.03	239.27	**0.351**		Selvage for both vein types	VA05074726	1.24
3	3	1.0	2.0	20		120.0	chl/s	5																					
																						B364396	BLANK		**<0.005**			VA05074726	
3	1	1.0	3.0	50	30	2.0	q/chl	3	0		2.0							2.0				B364397	239.27	240.80	**0.393**			VA05074726	1.53
5	1	1.2	4.5	70	45	2.0	q/cb	2		0.1	9.0				3.0				5.0			B364398	240.80	242.32	**0.628**		~5% aspy all alt'd to scorodite	VA05074726	1.52
4	1	2.0	6.0	45	30	2.0	q/cb	2	0		4.0											B364399	242.32	243.85	**0.304**			VA05074726	1.53
5	1	2.0	6.0	30	50	2.0	q/cb	2	0		9.0	0.1	0.1		0.1							B364400	243.85	245.36	**0.627**		Sulphides all found in vein	VA05074726	1.51
2	1	1.2	2.0	50		1.0	q/cb	3	1		2.0	0.1			0.1							B364401	245.36	246.89	**0.994**			VA05074726	1.53
1	3	2.0	2.0	50		3.0	q/cb	4	0		20.0	0.1																	
2	1	1.2	2.0	50		1.0	q/cb	3	1		2.0	0.1			0.1							B364402	245.36	246.89	**0.755**	DUP		VA05074726	1.53
1	3	2.0	2.0	50		3.0	q/cb	4	0		20.0	0.1																	
3	1	1.0	3.0	45		0.5	q	3			3.0	5.0							4.0			B364403	246.89	248.41	**1.1**			VA05074726	1.52
4	1	3.0	4.5	20	35	10.0	q/chl	4	1				0.1					5.0				B364404	248.41	249.94	**0.498**			VA05074726	1.53
5	1	5.0	8.5	40		2.0	q/cb	3		3.0	6.0	2.0	0.1									B364405	249.94	251.46	**3.88**			VA05074726	1.52
4	1	1.0	3.5	40		1.0	q/cb/chl	2	0		5.0											B364406	251.46	252.99	**0.43**			VA05074726	1.53
1	3	0.5	0.5	45		2.0	q/cb	4	0						0.1							B364407	252.99	254.51	**1.375**			VA05074726	1.52
3	1	1.0	2.5	50		0.0					2.0																		
3	1	1.0	2.2	50	40	0.5	q	3	0													B364408	254.51	256.03	**0.804**			VA05074726	1.52
1	3	0.4	0.4	40		1.0	q/cb	3	0		40.0																		
3	1	1.0	2.2	50	40	0.5	q	3	0													B364409	254.51	256.03	**0.8**	PD/CA		VA05074726	1.52
1	3	0.4	0.4	40		1.0	q/cb	3	0		40.0																		
																						B364410	STANDARD 7G		**4.87**	7G		VA05074726	
4	1	1.5	4.5	40		10.0	q/cb/s	5			10.0	1.0	4.0	5.0					2.0	3.0		B364411	256.03	257.56	**1.515**			VA05074726	1.53
2	1	0.5	1.0	50		0.0					6.0	0.1	4.0						1.0	2.0		B364412	257.56	259.09	**0.502**			VA05074726	1.53
4	1	0.1	4.2	45		1.5	q/cb/s	3	1		15.0									2.0		B364413	259.09	260.60	**1.865**			VA05074726	1.51
5	1	1.0	3.2	50	30	2.0	q/cb/s	4	1	3.0	4.0							5.0		2.0		B364414	260.60	262.13	**1.355**			VA05074726	1.53
4	1	0.5	2.0	40	35	2.0	q/cb/s	4	1	1.0	4.0							4.0				B364415	262.13	263.65	**0.601**			VA05074726	1.52
																						B364416	BLANK		**<0.005**			VA05074726	
3	1	0.5	1.5	45		0.4	q/cb	3	0		3.0								2.0			B364417	263.65	264.85	**0.592**			VA05074726	1.20
2	1	1.5	2.0	45		0.0																B364418	264.85	266.02	**0.913**			VA05074726	1.17
2	4	3.0	5.0	30	50	40.0	q/chl/cb	5		15.0								5.0											
3	1	0.5	1.5	45		0.5	q	3			2.0	0.1	2.0		0.1				3.0			B364419	266.02	266.70	**0.454**			VA05074726	0.68
2	1	0.5	1.0	50		1.0	q/cb	3			2.0											B364420	266.70	268.22	**0.102**			VA05074726	1.52
1	6	1.0	1.0	130		25.0			2																				
5	1	2.0	5.2	60	30	4.0	q/cb/s	4	1		3.0											B364421	268.22	269.75	**0.8**			VA05074726	1.53
5	1	2.0	5.2	60	30	4.0	q/cb/s	4	1		3.0											B364422	268.22	269.75	**0.526**	DUP		VA05074726	1.53
2	1	1.0	2.0	60	50	2.0	q/cb	3					0.1						5.0	5.0		B364423	269.75	271.28	**0.367**			VA05074726	1.53
2	1	0.5	1.0	75		1.0	q	5	0										5.0	5.0		B364424	271.28	272.56	**0.448**		Ox'd staining on selvages	VA05074726	1.28
4	6	1.0	1.8	60	100	18.0	chl/q	3	2	95.0								5.0											
2	1	30.0	31.5	45		8.0	chl/q	4		2.0			0.1				0.1					B364425	272.56	273.03	**0.202**		moly	VA05074726	0.47

DRILL LOG LEGEND - P1	DATE: Aug 14 - 20, 2005	PAGE 15 of 16	
DRILL HOLE # : **DG05-301C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		281.94	304.05	GND with very little alteration. Selvage size and intensity increase with sulphide content in veins.		1	1		1	
10		304.05	308.02	GND: Section is moderately to highly altered with carb/chl/ser and silicification; Overall color is blue-yellow green; Carb appears partially oxidized (yellow) in veins, veinlets and coarse grains in selvages.	1	2	3		2	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 14-20, 2006

LOGGED BY: M. Stone

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides									Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
3	1	1.0	2.2	50		2.0	q/cb	2			20.0	0.1	0.1									B364426	273.03	274.32	**0.193**		Sulph's replaced by mica?	VA05074726	1.29
1	6	3.0	3.0	45		0.0													5.0	5.0									
1	3	1.0	1.0	35		2.0	q/s/cb	4			10.0																		
4	1	1.0	3.0	50		2.0	q/cb	3	0		10.0		0.1									B364427	274.32	275.84	**0.608**		Aspy in selvage	VA05074726	1.52
3	1	1.2	3.4	40		18.0	q/chl/cb	5		5.0	7.0		0.1									B364428	275.84	277.36	**0.045**			VA05074726	1.52
3	1	1.2	3.4	40		18.0	q/chl/cb	5		5.0	7.0		0.1									B364429	275.84	277.36	**0.044**	PD/CA		VA05074726	1.52
																						B364430	STANDARD 4D		**0.469**	4D		VA05074726	
4	1	1.0	4.0	60	50	2.0	q/cb/chl	3	0		3.0											B364431	277.36	278.89	**0.236**			VA05074726	1.53
3	1	1.0	2.5	65	45	30.0	chl/q/cb	4	1	4.0	2.0		0.1				0.1					B364432	278.89	280.42	**0.434**			VA05074726	1.53
3	1	1.0	2.8	50		1.0	cb/q	2		2.0	2.0											B364433	280.42	281.94	**0.386**			VA05074726	1.52
3	1	0.5	1.5	65		4.0	q/chl	4			3.0											B364434	281.94	283.46	**0.578**			VA05074726	1.52
5	1	1.0	2.6	45	60	1.0	q/cb/chl	4	0		4.0								5.0	4.0		B364435	283.46	284.99	**0.438**			VA05074726	1.53
																						B364436	BLANK		**<0.005**			VA05074726	
6	1	1.0	5.0	40		3.0	q/cb	3			2.0		2.0						4.0			B364437	284.99	286.52	**1.215**			VA05074726	1.53
1	1	6.0	6.0			25.0	q/chl	5		20.0	25.0																		
							cb/s	3																					
1	1	1.0	1.0	50		0.0				4.0								5.0				B364438	286.52	288.04	**0.948**			VA05074726	1.52
1	3	1.0	1.0	5	5		5	/cb	3	0.0	1.0	5.0						5.0	1.0										
1	4	1.0	1.0	12		0.0				0.0																			
1	4	0.5	0.5	10		0.0				0.0												B364439	288.04	289.56	**0.081**			VA05074726	1.52
2	1	1.5	2.5	40	55	3.0	q	2	0		1.0				0.1														
1	3	2.0	2.0	50		8.0	q/chl/cb	3	1	0.1	0.1							5.0	5.0	5.0									
3	1	1.2	3.0	50		4.0	q/s	3														B364440	289.56	291.08	**2.01**			VA05074726	1.52
2	4	1.0	1.3	20	10						5.0		0.1						5.0										
1	1	1.5	1.5	50		70.0	q/chl/s	5	0		5.0											B364441	291.08	292.60	**0.201**			VA05074726	1.52
1	1	1.5	1.5	50		70.0	q/chl/s	5	0		5.0											B364442	291.08	292.60	**0.325**	DUP		VA05074726	1.52
2	1	2.0	3.0	40		40.0	q/s/chl	5		10.0			0.1					5.0				B364443	292.60	294.13	**0.359**		Sulph vein adj to qtz vn	VA05074726	1.53
1	6	0.5	0.5	40																									
2	1	1.2	2.2	50		4.0	q/chl/cb	4			3.0		0.1									B364444	294.13	295.66	**0.447**			VA05074726	1.53
4	1	0.6	2.0	50	70	4.0	q	2														B364445	295.66	297.18	**0.861**			VA05074726	1.52
3	3	1.5	3.7	50		6.0	q/cb	4			30.0																		
2	1	1.0	2.0	60		2.0	q	4			3.0	0.1										B364446	297.18	298.74	**0.398**			VA05074726	1.56
1	3	0.5	0.5	60		2.0	q/cb	5											5.0										
3	1	1.0	3.0	40	60	2.0	q/chl	3			5.0		1.0									B364447	298.74	300.23	**0.169**			VA05074726	1.49
5	1	1.0	5.0	60		6.0	q/chl	3	0		5.0											B364448	300.23	301.75	**0.564**			VA05074726	1.52
1	6	1.0	1.0	50		20.0	s/cb/chl	5	1	100.0								5.0											
5	1	1.0	5.0	60		6.0	q/chl	3	0		5.0											B364449	300.23	301.75	**0.695**	PD/CA		VA05074726	1.52
1	6	1.0	1.0	50		20.0	s/cb/chl	5	1	100.0								5.0											
																						B364450	STANDARD 5E		**1.295**	5E		VA05074726	
2	1	2.5	4.0	50		0.0					3.0		0.1									B364451	301.75	303.28	**0.521**			VA05074726	1.53
2	4	0.4	0.8	15		0.0				0.0																			
5	1	1.5	3.5	60		1.0	q/cb/chl	4		10.0	5.0											B364452	303.28	304.05	**0.478**			VA05074726	0.77
2	1	2.0	2.5	30	50	30.0	chl/cb	4	1	20.0								2.0				B364453	304.05	305.30	**0.215**			VA05074726	1.25
1	3	1.0	1.0	55		6.0	q/chl/cb	4	1	20.0								2.0											
1	1	1.0	1.0	20		30.0	chl/cb	4	1	2.0								5.0				B364454	305.30	306.31	**0.081**			VA05074726	1.01
2	3	0.5	0.8	60	45	20.0	chl/cb/q	4	1		2.0																		
3	1	2.5	3.3	70	50	20.0	cb/chl/q	3		3.0			2.0					5.0				B364455	306.31	307.17	**0.496**			VA05074726	0.86
																						B364456	BLANK		**<0.005**			VA05074726	
1	3	1.5	1.5	20		50.0	chl/cb	4		0.1								5.0				B364457	307.17	307.83	**1.08**			VA05074726	0.66
1	1	0.5	0.5	40		4.0	q/cb/chl	3			10.0		3.0																
1	3	0.8	0.8	25		40.0	chl/cb/q	4		10.0			0.1					3.0											

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-302C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1178m

BEARING: 000 | DIP: -50°

DATES DRILLING: Aug 1 - 5, 2005 | DATES LOGGING: Aug 21 - 28, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 460051 NORTHING: 7099266

COORD SYSTEM: NAD 83: EASTING: 459933 NORTHING: 7099451

NAD 27 (CORRECTED for historic grid): EASTING: 460021 NORTHING: 7099276

SECTION LINE (Historic Grid): 460025 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 0 - 4.57m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B363773 - B363853

Requisition #: MASP448STRGOL.05Q Date Shipped: 26-Aug-05

Lab Record #: VA05074725 Date Received: 2-Sept-05

Sample Sequence: B363854 - B363973

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Aug-05

Lab Record #: VA05074196 Date Received: 2-Sept-05

Sample Sequence: B363974 - B364052

Requisition #: MASP448STRGOL.05Q Date Shipped: 2-Sept-05

Lab Record #: VA05078596 Date Received: 15-Sept-05

Duplicates:	363782; 363802; 363822; 363842; 363862; 363902; 363922; 363942; 363962; 363982; 364002; 363422; 363442
Preparation Duplicate/ Check Assay:	363789; 363809; 363829; 363849; 363869; 363889; 363909; 363929 363949; 363969; 363989; 364009; 364029; 364049
Standards:	363870 (4D); 363810 (2B); 363830 (3C); 363850 (5E); 363870 (4D); 363890 (3C); 363910 (2B); 363930 (5E); 363950 (3C); 363970 (4D); 363990 (1A); 364010 (7G); 364030 (6F); 364050 (6F)
Blanks:	363776; 363796; 363816; 363836; 363856; 363876; 363896; 363916; 363936; 363956; 363976; 363996; 364016; 364036

FROM	TO	LITHOLOGY
0.00	4.57	Casing
4.57	306.92	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
76.20	341.2	-48.9	007.2	008.2
152.39	342.6	-49.2	008.6	009.6
228.59	342.9	-50.1	008.9	009.9
306.92	344.5	-50.2	010.5	011.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: Aug 21-28, 2005	PAGE 1 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00-4.57	0.00	4.57	Casing						
10	2.57-306.93	4.57	9.14	GND: Broken up, moderately limonitic GND; Oxidation occurs among fracture/vein selvages and fracture faces; Size of core ~5cm long on average; No other alteration apparent; Quartz veins commonly contain limonite stained vugs.	3					
10		9.14	29.26	GND: GND is less broken up than previous (4.57 - 9.14m); Limonite is more pervasive with interval of extremely oxidized GND; Edges of limonite are commonly remnant sericite +/- chlorite alteration overprinted by limonite; Intervals of unaltered grey GND are also common (ex. 20.90 - 21.64m); Quartz veins tend to be vuggy (~5%)	4					
10		29.26	70.32	GND: Grey GND that has undergone intensive oxidation; Oxidation appears to be associated with fractures (commonly cb/calcite filled) and overprints any previous alteration; Previous alteration can still be distinguished (rusty green) eg. 35.88 - 36.18m, oxidation, sericite alteration; Several intervals of unaltered grey GND are present (60cm max) 42.37 - 42.97m; Quartz vein in oxide selvages commonly have limonite stained vugs; From 48.77 - 50.29m core is extremely carbonate altered, crumbly to clayey and limonitic; Quartz veins tend to be small (2-4mm average) with low sulphide content; Low angle (~10° TCA) limonite carbonate lined fractures common throughout - possible fault gouge? (up to 0.5cm); At 69.23m - 8cm limonitic clay interval with polished (no slickenlines) face up hole, having sharp contact with limonite GND and gradual contact downhole at 30° TCA.	3					

DRILL LOG LEGEND P2

Selvages 0 = No Alteration, 5 = Intense Alt'n

Ox. State 0 = No Oxidized Sulphides, 5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biolite	other		From	To					
2	1	0.5	1.0	45						0.1								2.0				B363773	4.57	6.10	1.430			VA05074725	1.53
0																						B363774	6.10	7.62	0.067			VA05074725	1.52
3	1	0.3	0.8	45														10.0				B363775	7.62	9.14	0.624			VA05074725	1.52
																						B363776	BLANK		0.005			VA05074725	
3	1	0.3	0.7	45														10.0				B363777	9.14	10.67	0.139			VA05074725	1.53
3	1	0.5	1.0	45		0.5	q	3	4									10.0				B363778	10.67	12.19	0.325			VA05074725	1.52
1	3	0.5	0.5	45														20.0											
5	1	0.5	1.5	45	30	0.4	q	4	4									10.0				B363779	12.19	13.72	0.133			VA05074725	1.53
2	1	0.5	0.7	30	45					0.1								2.0				B363780	13.72	15.24	0.125			VA05074725	1.52
5	1	1.2	2.0			0.5	q	5	2		2.0	1.0						3.0				B363781	15.24	16.76	0.084			VA05074725	1.52
5	1	1.2	2.0			0.5	q	5	2		2.0	1.0						3.0				B363782	15.24	16.76	0.046	DUP		VA05074725	1.52
1	1	0.5	0.5	40														5.0				B363783	16.76	18.29	0.055			VA05074725	1.53
1	4	0.2	0.2	40		4.0	cb	3	4									50.0											
4	4	1.0	2.0	45	85	5.0	cb	3	4									75.0				B363784	18.29	19.81	0.092			VA05074725	1.52
3	1	0.5	1.0	45														5.0											
1	5	0.3	0.3	30							2.0											B363785	19.81	20.90	0.072			VA05074725	1.09
5	1	0.6	1.2	45		1.5	q/s	5	1		2.0											B363786	20.90	21.64	0.125			VA05074725	0.74
5	1	0.5	1.5	50														5.0				B363787	21.64	22.86	0.096			VA05074725	1.22
1	4	0.6	0.6	45														90.0											
8	1	0.5	3.0	45		0.3	q	4	2									4.0				B363788	22.86	24.38	0.101			VA05074725	1.52
1	4	0.8	0.8	45														90.0											
8	1	0.5	3.0	45		0.3	q	4	2									4.0				B363789	22.86	24.38	0.078	PD/CA		VA05074725	1.52
1	4	0.8	0.8	45														90.0											
																						B363790	STANDARD 4D		0.453	4D		VA05074725	
3	1	0.5	1.5	45		0.5	q	4	2	0.1								2.0				B363791	24.38	25.91	0.117			VA05074725	1.53
7	1	0.5	2.0	45		0.5	q	4	2		2.0		0.1					2.0				B363792	25.91	27.43	0.163			VA05074725	1.52
7	1	0.5	2.5	30		0.5	q/cb	4	3		2.0							5.0				B363793	27.43	29.26	0.090			VA05074725	1.83
2	3	2.5	2.7	30														50.0											
1	4	0.3	0.3	30														1.0											
2	1	0.5	1.0	30														5.0				B363794	29.26	30.48	0.160			VA05074725	1.22
1	3	0.5	0.5	45		1.5	s/chl	4	2									20.0											
5	1	0.5	2.2	45		1.5	s/chl	4	2									2.0				B363795	30.48	32.00	0.091			VA05074725	1.52
																						B363796	BLANK		<0.005			VA05074725	
4	1	0.5	2.0	45	60						1.0		1.0					5.0				B363797	32.00	33.53	0.136			VA05074725	1.53
2	1	1.0	1.2	45		3.0	s/cb	3	3									5.0				B363798	33.53	35.05	0.056			VA05074725	1.52
6	1	0.5	2.5	45		0.5	s/cb	4	4													B363799	35.05	36.58	0.117			VA05074725	1.53
1	3	1.0	1.0	45														90.0											
7	1	0.8	3.0	45	60	1.0	5	4	4		1.0		1.0					2.0				B363800	36.58	38.10	0.039			VA05074725	1.52
3	1	0.6	1.0	30	45						1.0		1.0					1.0				B363801	38.10	39.62	0.038			VA05074725	1.52
3	1	0.6	1.0	30	45						1.0		1.0					1.0				B363802	38.10	39.62	0.056	DUP		VA05074725	1.52
10	1	0.6	3.0	45	30	1.0	q	4	2		2.0		1.0					2.0				B363803	39.62	41.15	0.117			VA05074725	1.53
6	1	0.8	2.2	45	30						2.0	0.1	1.0					1.0				B363804	41.15	42.67	0.167			VA05074725	1.52
8	1	0.5	2.4	45							2.0		0.1					2.0				B363805	42.67	44.20	0.124			VA05074725	1.53
2	1	0.3	0.5	45		1.0	5	1	1									5.0				B363806	44.20	45.72	0.052			VA05074725	1.52
2	1	0.5	0.7	45		0.3	1	q	5	1.0								1.0				B363807	45.72	47.24	0.316			VA05074725	1.52
8	1	1.0	3.0	45	30													5.0				B363808	47.24	48.77	0.071			VA05074725	1.53
8	1	1.0	3.0	45	30													5.0				B363809	47.24	48.77	0.105	PD/CA		VA05074725	1.53
																						B363810	STANDARD 2B		3.000	2B		VA05074725	

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 3 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		70.32	100.58	GND: Grey GND similar to previous interval (29.26 - 70.32m) only limonite is less extensive, except locally at 79.85 - 80.4m where core is extremely limonitic with sharp contact @ 35° TCA; Non oxidized GND is more dominant where quartz veins occur in limonitic selvages, sulphides are oxidized and veins are left vuggy; Fracture faces still limonitic, commonly with carb/calcite; From 77.35 - 77.5m, 50% of core silicified with 5% biotite and 2 % acicular crystals (bismuth?) - slightly oxidized at edges of silicification - no observed sulphides; At 94.0m chl alteration is more intense around pyrrhotite then the rest of the quartz veins; Slickenlines @ 83.82m wi face at 30° and lines at 45°.	2					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 4 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B363811	48.77	49.75	0.145			VA05074725	0.98
0																						B363812	49.75	50.93	0.440			VA05074725	1.18
4	1	1.0	2.0	30	70													5.0				B363813	50.93	51.82	0.092			VA05074725	0.89
2	1	0.4	0.6	45														4.0				B363814	51.82	53.34	0.143			VA05074725	1.52
3	1	0.3	0.9	45														5.0				B363815	53.34	54.86	0.257			VA05074725	1.52
																						B363816	BLANK		0.006			VA05074725	
2	1	0.8	1.6	30														2.0				B363817	54.86	56.39	0.100			VA05074725	1.53
2	1	0.6	4.0	45														3.0				B363818	56.39	57.91	0.052			VA05074725	1.52
0																						B363819	57.91	59.44	0.079			VA05074725	1.53
4	1	0.3	0.9	35														4.0				B363820	59.44	60.96	0.038			VA05074725	1.52
2	1	0.4	0.6	40	30	0.6	q	3	1									2.0				B363821	60.96	62.48	0.021			VA05074725	1.52
2	1	0.4	0.6	40	30	0.6	q	3	1									2.0				B363822	60.96	62.48	0.033	DUP		VA05074725	1.52
2	1	0.5	1.0	45														2.0				B363823	62.48	64.01	0.034			VA05074725	1.53
5	1	0.5	2.0	45	30	0.3	q	4	1									2.0				B363824	64.01	65.53	0.175			VA05074725	1.52
1	1	0.8	0.8	35														5.0				B363825	65.53	67.06	0.063			VA05074725	1.53
1	1	0.8	0.8	30		0.5	s/q	4	3									10.0				B363826	67.06	68.58	0.205			VA05074725	1.52
1	3	0.5	0.5	30														50.0											
2	1	1.0	1.2	30														2.0				B363827	68.58	70.10	0.086			VA05074725	1.52
0																						B363828	70.10	70.32	0.039			VA05074725	0.22
0																						B363829	70.10	70.32	0.028	PD/CA		VA05074725	0.22
																						B363830	STANDARD 3C		0.094	3C		VA05074725	
2	1	0.3	0.5	45							0.1							1.0				B363831	70.32	71.63	0.044			VA05074725	1.31
1	3	0.3	0.3	45															2.0										
4	1	1.2	3.0	30		1.0	q/chl	5	0		0.1	0.1	0.1									B363832	71.63	72.14	2.250			VA05074725	0.51
2	1	0.3	0.5	30		0.5	q/chl	2	0		1.0											B363833	72.14	73.15	0.046			VA05074725	1.01
5	1	0.5	1.8	30							1.0											B363834	73.15	74.68	0.172			VA05074725	1.53
3	3	0.5	1.0	30		0.5	q/chl	2	0									2.0											
6	1	1.0	3.0	30							1.0	1.0						5.0				B363835	74.68	76.20	0.234			VA05074725	1.52
																						B363836	BLANK		<0.005			VA05074725	
2	3	1.0	1.5	30		1.5	q/chl	4			1.0											B363837	76.20	77.72	0.342			VA05074725	1.52
1	1	0.2	0.2	30																									
8	1	0.5	2.0	30		0.5	chl	5			1.0											B363838	77.72	79.25	0.207			VA05074725	1.53
3	1	0.3	0.9	45							1.0											B363839	79.25	79.85	0.024			VA05074725	0.60
3	1	1.0	1.6	45														5.0				B363840	79.85	80.40	0.085			VA05074725	0.55
6	1	1.0	3.5	35														5.0				B363841	80.40	82.30	0.109			VA05074725	1.90
6	1	1.0	3.5	35														5.0				B363842	80.40	82.30	0.134	DUP		VA05074725	1.90
1	1	0.3	0.3		30													5.0				B363843	82.30	83.82	0.040			VA05074725	1.52
1	4	0.2	0.2		45	1.0	chl	4	2									50.0											
3	1	0.4	1.0	10	30	1.0	chl	3										2.0				B363844	83.82	85.34	0.493			VA05074725	1.52
1	4	0.5	0.5	30		0.3	q/chl	5			1.0							2.0											
4	1	0.5	1.8	35							1.0							1.0				B363845	85.34	86.87	0.019			VA05074725	1.53
3	1	0.5	0.9	30		0.3	q	5			2.0	0.1	1.0									B363846	86.87	88.39	0.014			VA05074725	1.52
1	1	0.4	0.4	30														2.0				B363847	88.39	89.92	0.027			VA05074725	1.53
2	1	0.3	0.5	45	30	0.3	q	5			2.0		2.0					2.0				B363848	89.92	91.44	0.047			VA05074725	1.52
2	1	0.3	0.5	45	30	0.3	q	5			2.0		2.0					2.0				B363849	89.92	91.44	0.085	PD/CA		VA05074725	1.52
																						B363850	STANDARD 5E		1.435	5E		VA05074725	
4	1	0.2	0.8	40		0.5	q	3														B363851	91.44	92.96	0.054			VA05074725	1.52
1	6	1.0	1.0	30		1.0	chl/q	4					30.0					5.0											
4	1	0.5	1.2	30		1.0	q/chl	4			2.0		1.0					2.0				B363852	92.96	94.49	0.086			VA05074725	1.53
1	5	1.0	1.0	45		1.0	chl/q	4			2.0		2.0																
7	1	1.0	5.0	30		1.0	q/chl	3	2		1.0		1.0					1.0				B363853	94.49	96.01	0.153			VA05074725	1.52
9	1	0.6	3.0	30	40	1.0	chl/q	4			2.0		2.0									B363854	96.01	97.54	0.404			VA05074196	1.53
1	5	0.8	0.8	45		0.5	chl/q	3			2.0		10.0					2.0											
4	1	0.6	1.6	30		0.5	q/chl	3			2.0		2.0					1.0				B363855	97.54	99.06	0.245			VA05074196	1.52

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 5 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		100.58	116.52	GND: Grey GND where majority of core has been oxidized with unaltered to non oxidized core in intervals (similar to interval 29.26 - 70.32m); Limonite occurs on all fracture faces commonly with carbonate/calcite; Quartz veins with limonite selvages commonly contain oxidized vugs; Oxidation is moderate except locally as selvage for intensely oxidized, carbonitized and argillic altered interval at 105.47 (5cm) with grey quartz eyes (fault gg?); @ 101.61m ~1cm quartz vein at 30° TCA contains a massive, soft (2-3) black mineral (oxidation product?); Aspy found within black mineral, po and cpy also found in quartz vein; @ 108.44 - 108.77m there is abundant quartz veining or quartz blebs (avg 8x4cm) with 1-2% aspy and trace cpy, proximal to a 2cm quartz vein with 2% aspy.	3					
10		116.52	138.68	GND: Grey GND same as described in interval 70.32 - 100.58m; From 192.4 - 192.75m GND is slightly more mafic with no veining; @ 129.64m a 6cm interval of limonite, carb-rich clay altered GND with remnant quartz eyes; Sharp contact with competent GND at 30°; At 132.69m a 5cm cb-rich, slightly limonitic clay seam with rare <2mmx7mmx2mm quartz eyes, sharp irregular contact at 90°.	2					
10		138.68	141.30	GND is moderately limonitic throughout with locally more intensive selvages with slickenlines (141.08m with face at 40° and lines at 45°); Similar to interval 29.26 - 70.32m; Slickenlines 139.08 with face at 30° and lines at 45°.	3					
10		141.30	142.01	GND intensely oxidized to a rusty yellowish color; Core is soft and becomes softer down hole as argillic alteration intensifies; Core effervesces strongly where it has been altered to clay; Pale lim color possibly due to overprinting of previous alteration (ser?); Quartz veins tend to be irregular and discontinuous; Sharp contact at 142.01m at 45°.	4			4	3	
10		142.01	147.00	GND has undergone intense alteration; Core has a dark green color (chlorite + sericite alteration) but closely examined pale-green-grey (ser alteration); Core interchanges btwn extremely clay altered to slightly clay altered at shallow angles (1-30°); Speckled throughout is euhedral-subhedral, rusty-orange-brown (oxidized) siderite (1-10%); Siderite up to 4x4mm; Siderite dominates core (50%) locally from 142.01 - 142.26m and 146.25 - 146.77m; Quartz veins are broken up and commonly displaced or irregular - appear as breccias (angular quartz clasts randomly oriented).	3	5	5	5	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 6 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides									Oxidation					Sample Number	Interval						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B363856	BLANK		<0.005			VA05074196	
6	1	1.0	2.0	30		0.3	q/chl	3	2		1.0							4.0				B363857	99.06	100.58	0.367			VA05074196	1.52
5	1	1.0	3.0	30	40	1.0	q/chl	3	2		2.0	0.1	2.0									B363858	100.58	102.11	0.148			VA05074196	1.53
4	1	0.6	1.5	35		1.0	q/s	4	2									10.0				B363859	102.11	103.63	0.197			VA05074196	1.52
4	1	0.5	1.0	30		0.3	q/chl	3	2									2.0				B363860	103.63	105.16	0.078			VA05074196	1.53
6	1	2.0	3.5	40	30								1.0					5.0				B363861	105.16	106.69	0.423			VA05074196	1.53
6	1	2.0	3.5	40	30								1.0					5.0				B363862	105.16	106.68	0.151	DUP		VA05074196	1.52
5	1	0.5	1.6	30		0.2	chl	3	2		1.0		1.0					2.0				B363863	106.68	108.20	0.146			VA05074196	1.52
3	1	2.0	2.5	40									2.0					1.0				B363864	108.20	109.73	2.130			VA05074196	1.53
3	1	2.0	2.7	10	30	0.5	q	4					3.0				0.1					B363865	109.73	111.25	0.272		Mo only in one vein	VA05074196	1.52
2	1	0.2	0.4	30		1.0	q	4	3									5.0				B363866	111.25	112.78	0.088			VA05074196	1.53
3	1	0.6	1.5	20	30	0.2	q	5			2.0		1.0									B363867	112.78	114.30	0.352			VA05074196	1.52
2	1	0.5	1.0	30							2.0							2.0				B363868	114.30	115.82	0.024			VA05074196	1.52
2	1	0.5	1.0	30							2.0							2.0				B363869	114.30	115.82	0.027	PD/CA		VA05074196	1.52
																						B363870	STANDARD 4D		0.481	4D		VA05074196	
3	1	0.6	1.2	40		0.3	q	4	2		2.0							2.0				B363871	115.82	116.52	0.094			VA05074196	0.70
1	1	0.2	0.2	40																		B363872	116.52	117.35	0.196			VA05074196	0.83
6	1	0.6	2.2	40		1.0	chl	3										1.0				B363873	117.35	118.87	0.085			VA05074196	1.52
2	1	0.3	0.5	40		0.5	chl	3			2.0		1.0					1.0				B363874	118.87	120.40	1.730			VA05074196	1.53
1	3	0.3	0.3	40		1.0	5	2	2		2.0							10.0											
4	1	0.2	0.8	40		1.0	chl	2			2.0		5.0									B363875	120.40	121.92	0.233			VA05074196	1.52
																						B363876	BLANK		<0.005			VA05074196	
4	1	0.5	1.4	45							2.0	0.1	2.0									B363877	121.92	123.44	0.125			VA05074196	1.52
3	1	0.6	1.2	40	30						2.0	1.0	4.0									B363878	123.44	124.97	0.284			VA05074196	1.53
2	1	1.0	1.2	45							2.0		1.0									B363879	124.97	126.49	0.125			VA05074196	1.52
1	6	1.2	1.2	30		2.0	s/chl	4			2.0		50.0									B363880	126.49	128.02	0.278			VA05074196	1.53
3	1	0.3	0.7	30		0.5	chl	3			4.0		1.0																
2	3	0.4	0.6	30		0.5	q	5			2.0	0.1										B363881	128.02	129.54	0.043			VA05074196	1.52
1	1	0.2	0.2	45							2.0																		
2	3	0.4	0.6	30		0.5	q	5			2.0	0.1										B363882	128.02	129.54	0.140	DUP		VA05074196	1.52
1	1	0.2	0.2	45							2.0																		
0																						B363883	129.54	131.06	0.082			VA05074196	1.52
3	1	0.5	1.2	40	30	1.0	chl	4			2.0		5.0					2.0				B363884	131.06	132.59	1.725			VA05074196	1.53
2	1	0.5	1.0	40	30	0.3	q	4			1.0		1.0									B363885	132.59	134.11	0.069			VA05074196	1.52
4	1	0.5	1.5	40							2.0		1.0					2.0				B363886	134.11	135.64	0.434			VA05074196	1.53
6	1	0.8	2.5	40							1.0		1.0									B363887	135.64	137.16	0.111			VA05074196	1.52
5	1	0.5	2.2	40		1.0	q	5	2		1.0		1.0					2.0				B363888	137.16	138.68	0.349			VA05074196	1.52
5	1	0.5	2.2	40		1.0	q	5	2		1.0		1.0					2.0				B363889	137.16	138.68	0.386	PD/CA		VA05074196	1.52
																						B363890	STANDARD 3C		0.098	3C		VA05074196	
2	1	1.0	1.5	30														2.0				B363891	138.68	140.21	1.040			VA05074196	1.53
0																						B363892	140.21	141.30	0.285			VA05074196	1.09
1	1	1.0	1.0	30														2.0				B363893	141.30	142.01	0.123			VA05074196	0.71
3	1	2.0	3.0	45														5.0				B363894	142.01	143.57	14.650			VA05074196	1.56
4	1	3.0	8.0	30	45													5.0				B363895	143.57	144.90	5.950			VA05074196	1.33

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 7 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		147.00	153.87	GND moderately limonitic throughout as in interval 138.68 - 141.3m; Slickenlines: @ 150.4m face 20°/lines 25°; @ 151.1m face 30°/lines 60°; @ 149 m face 45°/lines 45° TCA; From 150.3 - 151.1m quartz veins are irregular +/- displaced. Limonite alteration is slightly more intense and locally appears blotchy.	3					
10		153.87	155.00	GND: 2 large white quartz veins that have been moderately fractured (carb filled frac's) with limonite faces; Very low sulphide content (tr aspy + py); Fracturing occurs at low angles (20-30°); Between veins is 5cm of sericite + oxidized GND with slickenlines at 154.18 m face 80°/lines 80° TCA: Contact at 155.0m is sharp at 25° with grey clay containing very fine grained disseminated pyrite and quartz eyes (2x2x2mm average).						
10		155.00	161.54	GND with extensive sericite alteration; Limonite staining along fractures is common; Speckled siderite (up to 4x4mm) and massive along fractures at 157.46m and 155.59m; @ 159.94m, 2 parallel quartz-sulphide veins, 0.5cm py vein and 2cm aspy vein. Pyrite vein is very fine to medium grained. Aspy vein is massive aspy; lim fractures occur in both veins but cross-cut fractures within GND; Slickenlines: @155.4m face at 60° with lines at 85°; @ 156.95m face at 30° with lines at 90°.						
10		161.54	170.69	GND: Grey GND with abundant quartz veining; Larger quartz veins tend to have selvages overprinted by oxidation (previous sericite alteration?); Limonite also occurs from fracturing; Possible fault gouge @ 167.25m at 20° (3cm gg adjacent to 1cm quartz vein); Limonite selvages are soft and slightly carbonate altered. Slickensides: @163.70m face at 30° with lines at 40°; @ 166.12m face at 75° with lines at 75°; @ 166.17m face at 30° with lines at 30°; @ 169.00m face at 40° with lines at 65° TCA.	3					
10		170.69	178.31	GND: Grey GND; Limonite+/- carbonate/calcite still appears on fracture faces; Locally core is limonite throughout from 172.51 - 172.81m where core is highly fractured; Limonite is becoming much less prominent; Slickensides: @172.41m face at 20° with lines at 45°; @ 173.0m face at 10° with lines at 10°; @ 176.68m face at 30° with lines at 90°; @ 176.66m face at 60° with lines at 90° TCA.	3					
10		178.31	180.22	GND: Sericite altered GND that has been oxidized; Locally core is very highly fractured and crumbly.	4	5		3		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B363896	BLANK		0.005			VA05074196	
1	1	2.5	2.5	45									2.0					5.0				B363897	144.90	146.16	0.123			VA05074196	1.26
5	1	1.5	5.0	30														4.0				B363898	146.16	147.00	0.933			VA05074196	0.84
2	1	2.0	3.0	45	50													2.0				B363899	147.00	148.70	1.120			VA05074196	1.70
6	1	2.0	5.0	30	60								0.1					2.0				B363900	148.70	150.30	0.653			VA05074196	1.60
1	1	0.4	0.4	60														1.0				B363901	150.30	151.10	0.770			VA05074196	0.80
1	1	0.4	0.4	60														1.0				B363902	150.30	151.10	0.301	DUP		VA05074196	0.80
5	1	1.0	3.2	45	30						0.1							1.0				B363903	151.10	152.40	0.447			VA05074196	1.30
2	1	0.5	1.0	30														2.0				B363904	152.40	153.87	0.481			VA05074196	1.47
1	3	0.5	0.5	30														1.0											
2	1	0.3	0.6	45									1.0									B363905	153.87	155.00	2.520			VA05074196	1.13
2	1	0.8	1.3	45									0.1					1.0				B363906	155.00	155.73	0.796			VA05074196	0.73
2	1	2.0	3.0	45									1.0					2.0				B363907	155.73	156.97	1.195			VA05074196	1.24
3	1	2.0	3.0	45									0.1					2.0				B363908	156.97	158.50	0.976			VA05074196	1.53
3	1	2.0	3.0	45									0.1					2.0				B363909	156.97	158.50	0.892	PD/CA		VA05074196	1.53
																						B363910	STANDARD 2B		3.240	2B		VA05074196	
4	1	1.6	45.0	30														2.0				B363911	158.50	159.94	0.299			VA05074196	1.44
2	6	2.5	4.5	30						30.0			30.0					5.0				B363912	159.94	160.02	13.450			VA05074196	0.08
4	1	1.2	2.4	30	40					5.0			4.0					4.0				B363913	160.02	161.54	0.527			VA05074196	1.52
2	3	0.5	0.7	35						5.0			6.0					5.0											
1	6	0.2	0.2	35						90.0								2.0											
7	1	2.0	7.0	30	70								0.1					0.1				B363914	161.54	162.84	0.280			VA05074196	1.30
7	1	6.0	16.0	30	45	7.0	s/cb	3	3				0.1					1.0				B363915	162.84	164.59	3.310			VA05074196	1.75
																						B363916	BLANK		<0.005			VA05074196	
3	1	2.0	6.0	30		3.0	5	4	3				1.0					1.0				B363917	164.59	166.12	0.380			VA05074196	1.53
1	5	0.4	0.4	30		1.0	q	5	2									1.0											
5	1	0.5	2.2	20	40	3.0	5	5	3				1.0					2.0				B363918	166.12	167.64	1.730			VA05074196	1.52
6	1	1.0	4.0	30	40	1.0	5	4			1.0		1.0					2.0				B363919	167.64	169.16	0.442			VA05074196	1.52
5	1	1.1	4.0	30		3.0	s/chl	4	2		1.0		2.0									B363920	169.16	170.69	2.300			VA05074196	1.53
1	3	0.6	0.6	40		2.0	s/chl	4		0.1																			
1	1	10.0	10.0	20		3.0	s/cb	4	3				2.0					1.0				B363921	170.69	171.28	15.550			VA05074196	0.59
1	1	10.0	10.0	20		3.0	s/cb	4	3				2.0					1.0				B363922	170.69	171.28	19.100	DUP		VA05074196	0.59
5	1	1.0	3.4	30	45	1.0	chl	4		2.0			1.0									B363923	171.28	172.21	0.146			VA05074196	0.93
3	1	1.5	2.5	40		1.5	5	5		0.1			2.0									**B363943**	172.21	173.74	0.282		Missed sample	VA05074196	1.53
1	5	0.4	0.4	40									1.0																
6	1	1.4	3.0	40		2.0	5	5		0.1	1.0		2.0									B363924	173.74	175.26	0.375			VA05074196	1.52
2	3	0.5	0.9	40		4.0	5	5																					
5	1	1.0	2.2	30		4.0	5	5														B363925	175.26	176.78	1.775			VA05074196	1.52
7	1	2.0	5.0	30		4.0	5	5	2				5.0									B363926	176.78	178.31	3.050			VA05074196	1.53
1	6	1.0	1.0	30		4.0	5	5	2	0.1			40.0																
0																						B363927	178.31	179.83	0.220			VA05074196	1.52
0																						B363928	179.83	180.22	1.135			VA05074196	0.39
0																						B363929	179.83	180.22	1.280	PD/CA		VA05074196	0.39
																						B363930	STANDARD 5E		0.960	5E		VA05074196	

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 9 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		180.22	181.89	GND: Grey GND with sericite and chlorite alteration; Core is competent; Quartz veins are minimal; Slickenlines: @180.8m face 50°, lines 70°.		4	3			
10		181.89	184.40	GND: Intensely clay and sericite alt'd GND; <2mm py/cb veinlets are common throughout; Fine grained disseminated pyrite occurs locally where core is most intensely altered; Sulphide veins (py) contain dark grey clay (oxidized sulphides?); Core appears brecciated (183.9 - 184.4m) quartz veins are broken up and displaced and crumbly with abundant disseminated pyrite in dark grey clay matrix; Blocks of brecciated (?) core have slickenlines with pyrite smearing.		5		4		
10		184.40	189.22	GND: Highly broken-up and fractured grey GND (longest piece is 12cm); Some blocks appear sericitized; Slickenlines: @187.45m Face at 30° with lines at 70° TCA.						
10		189.22	192.02	GND: Intensely clay and sericite altered GND; Similar to previously described from interval 181.89-184.4m		5		5		
10		192.02	202.91	GND: GND has undergone various degrees of sericite alteration due to fracturing as altered GND tends to have sharp contacts with grey clay and disseminated pyrite or sheared pyrite on slip face; Alteration may be gradual at one end, and sharp at the other end of alteration selvage; K-spar/quartz veins are present, and within sericite selvages are k-spar, and euhedral pyrite xtls; K-spar veins contain some carbonate; No limonite; Slickenlines: @193.80m face at 20°, lines at 60°; @ 196.65m face at 10°, lines at 30°; @ 197.9m face at 45°, lines at 85°; @ 199.1m face at 60°, lines at 85°; @ 199.12m face at 30°, lines at 60°; @ 201.67m face at 5°, lines at 25°.		4				
10		202.91	205.74	GND: Pale green GND; K-Spar alteration appears as selvages, veinlets, and euhedral crystals disseminated throughout; Quartz veins tend to be at very shallow angles; Non K-spar altered core (sericite alteration) is softer than K-altered core; Slickenlines: @205.00m face is at 5° with lines at 50° TCA; Possible sericite overprinting giving K-spar alteration greenish hue?; Quartz veins are commonly irregular +/- displaced.		5				5
10		205.74	210.73	GND: Broken core; @ 205.74 - 207.26m = GND has undergone sericite alteration (4cm selvage avg); @ 207.26 - 210.73m = GND has undergone clay alteration, blocks are smaller and consist of quartz veins and quartz selvages; @ 210.41 - 210.73m = Clay is carb-rich (strong HCL reaction).				4		
10		210.73	216.41	GND: The majority of the GND is sericite altered with scattered euhedral K-spar and veinlets of K-spar throughout; Intervals where GND is not altered (up to 30cm) it is finer grained and darker than normal grey GND.		5				3

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 10 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.5	0.8	40						2.0			2.0									B363931	180.22	181.89	0.271			VA05074196	1.67
2	3	1.0	1.5	20	40					2.0			2.0																
0																						B363932	181.89	182.36	0.272			VA05074196	0.47
4	1	1.0	3.0	5	45					10.0			5.0									B363933	182.36	182.88	5.130			VA05074196	0.52
1	6	0.3	0.3	5						40.0																			
0																						B363934	182.88	184.40	3.500			VA05074196	1.52
6	1	2.0	4.0	60	45					5.0			3.0									B363935	184.40	185.93	3.350			VA05074196	1.53
2	6	0.4	0.8	60	45					50.0								1.0											
																						B363936	BLANK		0.010			VA05074196	
2	1	2.0	3.0	45		1.0	s	5					0.1									B363937	185.93	187.45	1.165			VA05074196	1.52
1	3	0.5	0.5	45		1.0	5	4																					
2	1	1.0	1.8	60									4.0									B363938	187.45	189.22	0.893			VA05074196	1.77
1	3	0.4	0.4	60		1.0	s	5					1.0																
0																						B363939	189.22	190.50	0.437			VA05074196	1.28
0																						B363940	190.50	192.02	0.715			VA05074196	1.52
3	1	2.5	5.0	30	45					2.0			2.0									B363941	192.02	193.55	1.150			VA05074196	1.53
3	1	2.5	5.0	30	45					2.0			2.0									B363942	192.02	193.55	0.943	DUP		VA05074196	1.53
																						B363943	SEE ABOVE				Missed sample, see above (171.26-172.21m)		
4	1	1.0	3.0	55						1.0	1.0											B363944	193.55	195.07	0.220			VA05074196	1.52
1	2	0.5	0.5	45						1.0																			
3	2	0.5	1.2	55		2.0	s/k	5		2.0			1.0									B363945	195.07	196.46	0.141			VA05074196	1.39
1	1	0.2	0.2	45							0.1																		
0																						B363946	196.46	196.82	0.217			VA05074196	0.36
6	1	0.5	1.8	60	45	3.0	k/s	5		2.0												B363947	196.82	198.31	0.902			VA05074196	1.49
2	1	0.5	0.8	50		1.0	s/k	4			1.0											B363948	198.31	199.64	0.382			VA05074196	1.33
2	1	0.5	0.8	50		1.0	s/k	4			1.0											B363949	198.31	199.64	0.352	PD/CA		VA05074196	1.33
																						B363950	STANDARD 3C		0.095	3C		VA05074196	
8	1	1.0	3.5	50		2.0	5	3			2.0		1.0									B363951	199.64	201.17	0.327			VA05074196	1.53
2	1	0.4	0.6	30	45																	B363952	201.17	202.88	0.466			VA05074196	1.71
2	2	0.8	1.4	45		1.0	k/s	5																					
4	1	2.0	3.0	30	45																	B363953	202.88	204.22	0.763			VA05074196	1.34
1	2	0.4	0.4	30																									
7	1	1.0	2.5	20	10	4.0	k/s	5		0.1												B363954	204.22	205.74	1.795			VA05074196	1.52
2	1	0.3	0.6	45																		B363955	205.74	207.26	0.419			VA05074196	1.52
																						B363956	BLANK		<0.005			VA05074196	
2	1	0.4	0.7	45							2.0											B363957	207.26	209.79	0.709			VA05074196	2.53
0																						B363958	209.79	209.70	0.149			VA05074196	-0.09
0																						B363959	209.70	210.73	0.334			VA05074196	1.03
3	1	8.0	10.0	60		34.0	k/s	5		0.1			2.0									B363960	210.73	211.40	2.320			VA05074196	0.67
2	2	1.0	1.5	45																									
2	1	0.5	1.0	45																		B363961	211.40	213.10	0.084			VA05074196	1.70
1	2	1.5	1.5	55		7.0	s	5																					

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 11 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		216.41	220.45	GND: GND is highly broken up and sericite altered; GND is broken into 4x6x4 cm pieces with argillic alteration; Locally, pieces appear darker green due to chlorite alteration; Quartz veining is minimal; K-spar veinlets are present; Cavings present at 219.62m.		5	3			
10		220.45	222.50	GND: Darker, finer grained GND; Sericite selvages occur along k-spar +/- quartz +/- cb or fractures; Fractures typically have dark-grey-green (chloritic) clay faces; @ 222.09m is a 0.5cm quartz-k spar vein where k-spar is more pink than typical k-spar; Slickenlines: @222.25m with face at 45° and lines at 45°.		5				2
10		222.50	235.24	GND: Similar to previous interval (220.45 - 222.5m) but GND is typical with only local darker, finer grained GND (up to 25cm); Slickenlines: @ 224.03m with face at 65° and lines at 65°.		5				2
10		235.24	242.62	GND: Quartz-rich Granitoid (silicified); Fine grained and very hard; Carbonate fractures are abundant with sericite alteration selvages; Quartz veins are white with clean and sharp contacts with selvages; Slickenlines: @237.84m face at 25° with lines at 40°; @ 239.15m face at 70° with lines at 80°; @ 241.75m with face at 70° with lines at 75° TCA. Silicification (4).						4
10		242.62	259.08	GND: Back into Grey GND with intervals of sericite alteration commonly speckled with k-spar crystals (subhedral); K-spar veins and veinlets common within sericite alteration; Contact with quartz-rich GND is sharp at 50° TCA; @ 247.9m a 10cm zone of intense alteration appears brecciated (dark and light clay veinlets with minor disseminated pyrite); Slickenlines: @ 243.0 face at 10° with lines at 30° TCA; @ 254.31m face at 30° with lines at 85°; @ 254.1m a 1cm quartz vein is displaced twice by 2 dextral slips, the slip plane is on 0.8cm k-spar vein (possibly with carbonate), the slip planes are at 40° and 15°; Slickenlines: @ 255.95m face at 10°, lines at 40°. From 257.90 to 259.08m core is highly clay altered (crumbly) and quartz veins are crumbling.		5				2

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval					
						Selvages				Sulphides									Oxidation					Sample Number						
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	1	0.5	1.0	45																		B363962	211.40	213.10	0.091	DUP		VA05074196	1.70
1	2	1.5	1.5	55		7.0	s	5																						
1	1	0.5	0.5	70						5.0												B363963	213.10	213.84	0.286			VA05074196	0.74
1	2	1.5	1.5	30																										
0																						B363964	213.84	214.88	0.308			VA05074196	1.04
0																						B363965	214.88	216.41	0.033			VA05074196	1.53
0																						B363966	216.41	217.93	0.124			VA05074196	1.52
1	1	1.0	1.0	20						2.0												B363967	217.93	219.46	0.398			VA05074196	1.53
2	1	1.2	1.7	20	5					1.0												B363968	219.46	220.45	0.485			VA05074196	0.99
2	1	1.2	1.7	20	5					1.0												B363969	219.46	220.45	0.481	PD/CA		VA05074196	0.99
																						B363970	STANDARD 4D		0.475	4D		VA05074196	
3	2	1.5	2.2	45	30	14.0	s/k	5		5.0												B363971	220.45	221.70	0.115			VA05074196	1.25
2	1	0.5	1.0	45						2.0																				
1	1	2.0	2.0	70																		B363972	221.70	222.50	0.092			VA05074196	0.80
1	2	0.5	0.5	80						0.1																				
2	1	0.3	0.5	30							1.0											B363973	222.50	224.03	0.030			VA05074196	1.53
1	3	0.3	0.3	30						2.0																				
4	2	2.0	2.6	30		3.0	s	5		1.0												B363974	224.03	225.55	0.170			VA05078596	1.52
3	1	2.0	3.0	30		2.0	s	5					1.0									B363975	225.55	227.08	0.373			VA05078596	1.53
																						B363976	BLANK		<0.005			VA05078596	
0																						B363977	227.08	228.60	0.143			VA05078596	1.52
1	6	0.4	0.4	60						80.0												B363978	228.60	230.12	0.059			VA05078596	1.52
3	1	2.0	3.0	45						1.0												B363979	230.12	231.65	0.043			VA05078596	1.53
1	4	0.5	0.5	45																										
2	1	0.5	0.5	45	70					1.0												B363980	231.65	233.17	0.050			VA05078596	1.52
2	1	2.0	3.5	30		2.0	s	5		1.0												B363981	233.17	234.15	0.078			VA05078596	0.98
2	1	2.0	3.5	30		2.0	s	5		1.0												B363982	233.17	234.15	0.226	DUP		VA05078596	0.98
3	1	2.0	3.2	30	45	2.0	s	5		0.1												B363983	234.15	235.24	0.178			VA05078596	1.09
1	1	0.5	0.5	30							1.0											B363984	235.24	236.22	0.037			VA05078596	0.98
5	1	0.5	0.5	70		2.0	s	5		2.0	1.0											B363985	236.22	237.74	0.108			VA05078596	1.52
5	1	2.0	4.0	70		1.5	s	5		12.0	1.0											B363986	237.74	239.27	0.182			VA05078596	1.53
3	1	2.0	3.0	70		1.5	s	5		0.1			0.1									B363987	239.27	240.79	0.186			VA05078596	1.52
7	1	2.0	6.0	70	60	2.0	s	5			0.1											B363988	240.79	242.62	0.178			VA05078596	1.83
5	2	3.0	7.0	70		2.0	s	5			0.1																			
7	1	2.0	6.0	70	60	2.0	s	5			0.1											B363989	240.79	242.62	0.218	PD/CA		VA05078596	1.83
5	2	3.0	7.0	70		2.0	s	5			0.1																			
																						B363990	STANDARD 1A		0.792	1A		VA05078596	
5	1	2.0	4.5	60	50						0.1		0.1									B363991	242.62	243.81	0.152			VA05078596	1.19
1	2	1.0	1.0	50																										
3	2	0.6	1.1	10	60					1.0												B363992	243.81	245.36	0.462			VA05078596	1.55
4	1	1.0	3.0	60																										
4	1	1.0	3.0	50	60					0.1												B363993	245.36	246.89	0.164			VA05078596	1.53
2	2	1.0	1.5	40	60	5.0	s/k	5																						
3	1	1.0	2.0	45	60						1.0											B363994	246.89	248.41	0.081			VA05078596	1.52
2	2	1.0	1.2	45	60	8.0	s/k	5		1.0																				
4	1	2.0	4.0	60		2.0	s/k	5														B363995	248.41	249.94	0.180			VA05078596	1.53

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 13 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		259.08	266.90	GND: Back into q-rich granodiorite (silicified) as previously described; Core has less sericite alteration; Contact with grey GND is crumbled; Abundant carbonate fractures/veinlets; K-spar is no longer visible; core is moderately broken up (8cm avg) by steep (60-90°) fractures; Quartz veins are white and clean and commonly fractured adjacent to edges; Quartz veins appear to be post alteration; @ 260.7m coarse grained aspy vein (0.8cm) has crumbled away from 80° face; @ 265.28-265.89m core appears brecciated (quartz vein is broken up and crumbly with fine grained euhedral disseminated veinlets).		5				
10		266.90	272.80	GND: GND is intensely sericite and argillic altered; Core is a pale green colour and very soft; Possibly k-spar alteration was overprinted by sericite alteration as core is beige-green adjacent to veins but still soft; Quartz veins are commonly broken up and crumbly; No observed carbonate/calcite in quartz vein fractures or in GND; @ 268.22m, 16cm quartz vein with grey veinlets throughout contains up to 2.5x2.5x2mm euhedral disseminated pyrite (broken up at either end, no orientation); Slickenlines: @ 267.2m face at 40° with lines at 45° TCA.		5		5		
10		272.80	275.84	GND: GND has been completely sericite altered; Core is harder, darker and more competent than previous interval; Fractures and fracture faces filled with carbonate (less reactive than previously observed).		5		1		
10		275.84	281.12	GND; GND is completely sericite altered with moderate to intense clay alteration; Slickenlines: @ 279.68m face at 30° with lines at 90°.		5		3		
10		281.12	282.23	GND: GND with sericite alteration due to fracturing (carbonate filled fractures)		4				
10		282.23	283.46	GND: Unaltered (slightly more mafic) GND; Fine grained.						
10		283.46	285.51	GND: Unaltered grey GND; Moderate fracturing.						
10		285.51	288.04	GND: Grey GND that has undergone moderate clay alteration; Locally, intensely altered to clay with quartz eyes; Grey-dark grey (2-4mm) clay veins are common at 45° TCA; Slickenlines: @ 287.5m face at 10° with lines at 80°.				4		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 14 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	2	1.5	1.5	50		2.0	s/k	5																						
																						B363996	BLANK		<0.005			VA05078596	
5	1	1.5	35.0	40		1.0	s	2			4.0											B363997	249.94	251.46	0.170			VA05078596	1.52
2	2	0.8	1.4	60		1.0	s/k	5																						
4	1	1.0	2.2	60							1.0											B363998	251.46	252.98	0.280			VA05078596	1.52
3	2	3.0	4.5	40	45	5.0	s/k	5																						
4	1	1.0	3.0	40							1.0											B363999	252.98	254.51	0.174			VA05078596	1.53
3	2	0.6	1.6	40	15					1.0																				
3	1	0.5	1.4	60						1.0												B364000	254.51	256.03	1.720			VA05078596	1.52
3	2	0.8	1.4	30	60	3.0	s/k	5																						
1	1	1.0	1.0	60																		B364001	256.03	257.56	0.065			VA05078596	1.53
1	2	0.4	0.4	45		1.0	s	4					0.1																	
1	1	1.0	1.0	60																		B364002	256.03	257.56	0.114	DUP		VA05078596	1.53
1	2	0.4	0.4	45		1.0	s	4					0.1																	
3	1	2.0	4.0	60	30																	B364003	257.56	259.08	0.156			VA05078596	1.52
9	1	4.0	15.0	85	60																	B364004	259.08	260.60	0.959			VA05078596	1.52
7	1	2.0	5.0	80						0.1												B364005	260.60	262.13	0.182			VA05078596	1.53
1	6	0.8	0.8	80																										
2	1	1.0	1.5	70						1.0												B364006	262.13	263.25	0.206			VA05078596	1.12
6	1	1.0	4.0	70						1.0												B364007	263.25	265.28	0.164			VA05078596	2.03
3	1	4.0	8.0	45						10.0												B364008	265.28	265.89	0.344			VA05078596	0.61
3	1	4.0	8.0	45						10.0												B364009	265.28	265.89	0.365	PD/CA		VA05078596	0.61
																						B364010	STANDARD 7G		4.460	7G		VA05078596	
6	1	0.5	2.5	65						0.1												B364011	265.89	266.90	0.269			VA05078596	1.01
18	2	4.0	18.5	40						10.0			0.1									B364012	266.90	268.22	5.760			VA05078596	1.32
1	6	1.0	1.0	40						10.0			20.0								70.0									
1	1	16.0	16.0							10.0												B364013	268.22	268.38	6.110			VA05078596	0.16
1	1	4.5	4.5	60						0.1			0.1									B364014	268.38	269.75	0.685			VA05078596	1.37
2	1	1.0	2.0	30																		B364015	269.75	271.27	0.722			VA05078596	1.52
																						B364016	BLANK		<0.005			VA05078596	
2	1	0.2	0.4	30																		B364017	271.27	272.80	0.470			VA05078596	1.53
4	1	1.5	4.0	60						0.1												B364018	272.80	274.32	0.229			VA05078596	1.52
3	1	1.0	2.5	45																		B364019	274.32	275.84	0.904			VA05078596	1.52
1	1	0.5	0.5	10																		B364020	275.84	277.00	0.051			VA05078596	1.16
1	1	2.0	2.0	30						0.1												B364021	277.00	278.50	0.558			VA05078596	1.50
1	1	2.0	2.0	30						0.1												B364022	277.00	278.50	0.900	DUP		VA05078596	1.50
1	1	0.5	0.5	30																		B364023	278.50	279.68	1.535			VA05078596	1.18
0																						B364024	279.68	280.42	0.070			VA05078596	0.74
0																						B364025	280.42	281.12	0.099			VA05078596	0.70
0																						B364026	281.12	282.23	0.094			VA05078596	1.11
1	1	0.4	0.4	30																		B364027	282.23	283.46	0.046			VA05078596	1.23
1	4	0.5	0.5	30																										
6	1	1.0	2.5	30	45					1.0	2.0		0.1									B364028	283.46	284.79	0.158			VA05078596	1.33
6	1	1.0	2.5	30	45					1.0	2.0		0.1									B364029	283.46	284.79	0.200	PD/CA		VA05078596	1.33
																						B364030	STANDARD 6F		2.050	6F		VA05078596	
2	1	0.5	0.9	30							2.0	0.1										B364031	284.79	285.51	0.020			VA05078596	0.72
1	1	0.3	0.3	60														1.0				B364032	285.51	286.51	0.445			VA05078596	1.00

DRILL LOG LEGEND P1	DATE: Aug 21-28, 2005	PAGE 15 of 16	
DRILL HOLE # : DG05-302C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		288.04	290.40	GND: Unaltered Grey GND; Moderate - abundant carbonate fractures; Carbonate in fractures have greenish hue - chlorite/sericite?						
10		290.40	295.15	GND: Clay altered grey GND - similar to interval 285.51 - 288.04m; Slightly less altered; Unaltered intervals of GND common (up to 25cm); Locally carbonate alteration occurs at 292.08 - 292.37m.				3		
10		295.15	298.70	GND: Grey GND with moderate clay alteration and slight carbonate alteration.				3	1	
10		298.70	306.93	GND: Sericite altered GND; Differing shades of green due to different amounts of carbonate; Hardness is consistent; @ 306.5-306.9m slight clay alteration (softer and lighter core); Slickenlines @ 306.78m with face at 70° and lines at 75° TCA.		4				
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: Aug 21-28, 2005

LOGGED BY: K. Piepgrass

PAGE 16 of 16

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max. (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	6	0.3	0.3	45						50.0																				
7	1	2.0	6.0	60																		B364033	286.51	288.04	**1.140**			VA05078596	1.53
4	1	1.0	3.0	50							0.1											B364034	288.04	289.56	**0.265**			VA05078596	1.52
3	1	1.0	1.5	50	45						1.0											B364035	289.56	290.40	**0.255**			VA05078596	0.84
																						B364036	BLANK		**<0.005**			VA05078596	
3	1	1.0	2.5	60																		B364037	290.40	291.08	**0.091**			VA05078596	0.68
1	1	1.2	1.2	55																		B364038	291.08	292.61	**0.073**			VA05078596	1.53
5	1	1.0	3.0	45																		B364039	292.61	294.13	**0.593**			VA05078596	1.52
2	1	1.4	2.0	45							1.0											B364040	294.13	295.15	**0.253**			VA05078596	1.02
3	1	1.0	2.0	50																		B364041	295.15	296.28	**0.159**			VA05078596	1.13
3	1	1.0	2.0	50																		B364042	295.15	296.28	**0.254**	DUP		VA05078596	1.13
4	1	4.5	6.0	45							0.1											B364043	296.28	297.18	**0.434**			VA05078596	0.90
1	6	0.5	0.5	60		2.5	q	5		25.0			15.0																	
2	1	2.0	3.0	60						1.0												B364044	297.18	298.70	**0.201**			VA05078596	1.52
9	1	4.0	12.0	60	45					1.0												B364045	298.70	300.23	**1.010**			VA05078596	1.53
1	6	2.0	2.0	50						25.0			50.0																	
2	1	3.0	4.0	60						0.1			0.1									B364046	300.23	301.75	**0.085**			VA05078596	1.52
0																						B364047	301.75	303.28	**0.123**			VA05078596	1.53
7	1	10.5	14.0	70		6.0	5	5		1.0	1.0		1.0									B364048	303.28	304.80	**0.996**			VA05078596	1.52
7	1	10.5	14.0	70		6.0	5	5		1.0	1.0		1.0									B364049	303.28	304.80	**1.025**	PD/CA		VA05078596	1.52
																						B364050	STANDARD 6F		**2.790**	6F		VA05078596	
7	1	5.0	8.5	70						1.0												B364051	304.80	306.32	**0.253**			VA05078596	1.52
																						B364052	306.32	306.93	**0.177**			VA05078596	0.61
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-303C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1139m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 5 - 10, 2005 | DATES LOGGING: August 21-26, 2005

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459958 NORTHING: 7099268

COORD SYSTEM: NAD 83: EASTING: 459839 NORTHING: 7099454

NAD 27 (CORRECTED for historic grid): EASTING: 459928 NORTHING: 7099278

SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 11.0 m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B364458 - B364536

Requisition #: MASP448STRGOL.05Q Date Shipped: 29-Aug-05

Lab Record #: VA05074738 Date Received: 2-Sept-05

Sample Sequence: B364537 - B364620

Requisition #: MASP448STRGOL.05Q Date Shipped: 2-Sept-05

Lab Record #: VA05078597 Date Received: 15-Sept-05

Sample Sequence: B364621 - B364699

Requisition #: MASP448STRGOL.05Q Date Shipped: 6-Sept-05

Lab Record #: VA05074738 Date Received: 21-Sept-05

Duplicates:	364462; 364482; 364502; 364522; 364542; 364562; 364582; 364602; 364622; 364642; 364662; 364682
Preparation Duplicate/ Check Assay:	364469; 364489; 364509; 364529; 364549; 364569; 364589; 364609; 364629; 364649; 364669; 364689
Standards:	364470 (1A); 364490 (6F); 364510 (6F); 364530 (4D); 364550 (3C); 364570 (1A); 364590 (4D); 364610 (7G); 364630 (5E); 364650 (2B); 364670 (7G); 364690 (5E)
Blanks:	364476; 364496; 364516; 364536; 364556; 364576; 364596; 364616; 364636; 364656; 364676; 364696

FROM	TO	LITHOLOGY
0.00	11.00	Casing
11.00	292.61	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
30.48	334.10	-50.20	0.10	1.10
109.72	332.00	-49.80	358.00	359.00
201.16	334.30	-48.00	0.30	1.30
292.59	337.10	-46.10	3.10	4.10

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2005	PAGE 1 of 12		
DRILL HOLE # : DG05-303C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 11.0	0.00	11.00	Casing						
10	11.00 - 292.61	11.00	18.29	GND: Weathered GND, 70% reduced to coarse sand and gravel texture; Competent core not longer than 8cm; Colour of clay is variable: at 12.0m it is orange-med brown, at 16.4m it is light yellowish orange and at 16.4m it is whitish yellow. Competent GND is oxidized to med brown but original texture still present; Hematite makes up 1-10% of veins in this section, 100% oxidized.	4			3	2	
10		18.29	24.08	GND: Sheeted quartz veins at 60° TCA crosscut by veinlets of limonite at 140° TCA; These veinlets have wide selvages - up to 4cm oxidized zones and appear to be later than the quartz veins. From 23.1 to 23.3m, rock is crumbly orangey brown oxidized clay-fine sand; Rest of the section is competent, solid GND with oxidation/alteration surrounding veins and veinlets; From 23.8 to 24.08m, competent core is completely oxidized and GND texture is erased to a uniform orangey brown.	3			1	1	
10		24.08	36.58	GND: Highly altered and oxidized GND; 70% clay to sand texture, crumbly, no structure seen, light to medium brown; Even within competent core, original GND is 70% erased to an aphanitic oxidized and sericitized state; Evidence of brittle-ductile shear movement (sinistral) of quartz veins and slickensides in oxidation products on fracture faces (py, hem).	4	3	2	3	3	
10		36.58	45.72	GND: Highly oxidized and moderately altered GND. All competent. From 43.6 - 45.7m rock is medium brown and aphanitic; GND Texture totally erased and sericitic alteration visible beneath.	3	2	1	1	2	
10		45.72	48.50	GND: Moderate alteration and oxidation zone; Competent core with GND texture (med grained).	3	1			1	
10		48.50	51.82	GND: Oxidized and carbonitic GND; Very broken up to sandy texture over 10%; Limonite (including calcite) fill fractures, brecciating rock into <10cm pieces; At least 2 generations of quartz veining: (1) 0.5cm at 40° contains >10% hematite, often weathered out, always rusty brown stained; and (2) >1cm, higher angle, usually broken up/brecciated by late limonite veining.	4	1		2	3	
10		51.82	64.01	GND: Little carbonate, less oxidation in competent core; GND texture preserved except in narrow selvages around frequent veins; Minor foliation development at 60° TCA and slickensides in sericite/carbonate on ~0° TCA fracture faces.	3				1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 6 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B364458	11.00	12.19	**0.810**			VA05074738	1.19
2	1	1.0	1.5	40		1.0	q/cb	2	3	2.0								5.0				B364459	12.19	13.72	**0.051**			VA05074738	1.53
0																						B364460	13.72	15.24	**0.052**			VA05074738	1.52
4	1	1.5	5.0	70		4.0	q/cb	5	4	0.1								5.0				B364461	15.24	16.76	**0.072**			VA05074738	1.52
4	1	1.5	5.0	70		4.0	q/cb	5	4	0.1								5.0				B364462	15.24	16.76	**0.054**	DUP		VA05074738	1.52
13	1	1.0	2.0	75	35	1.0	q/cb	2	4													B364463	16.76	18.29	**0.041**			VA05074738	1.53
2	3	1.0	1.4	45		2.0	q/cb	3	2																				
6	1	1.0	5.0	60		2.0	q/cb	4	4		4.0					0.1						B364464	18.29	19.81	**0.128**			VA05074738	1.52
5	1	1.0	5.0	60		2.0	q/cb	2	2		4.0											B364465	19.81	21.34	**0.091**			VA05074738	1.53
1	3	0.3	0.3	70		1.0	q/cb	4	0		2.0		5.0						4.0										
5	1	2.0	5.0	55		1.0	q/cb	3	4		4.0		2.0		2.0							B364466	21.34	22.86	**0.095**			VA05074738	1.52
1	1	0.5	0.5	50		0.5	q/cb	4	3		1.0				1.0			5.0				B364467	22.86	24.08	**0.643**			VA05074738	1.22
3	1	1.0	2.5	70	50	4.0	q/cb	3	4	0.1								5.0				B364468	24.08	25.00	**0.160**			VA05074738	0.92
3	1	1.0	2.5	70	50	4.0	q/cb	3	4	0.1								5.0				B364469	24.08	25.00	**0.142**	PD/CA		VA05074738	0.92
																						B364470	STANDARD 1A		**0.978**	1A		VA05074738	
4	3	2.0	7.0	60	45	2.0	q/cb	4	3	1.0								5.0				B364471	25.00	25.91	**0.068**			VA05074738	0.91
2	1	0.9	1.8	40	120	0.0				0.1					0.1			5.0				B364472	25.91	27.43	**0.162**			VA05074738	1.52
3	3	1.2	2.6	45		2.0	q/cb	4	4																				
1	1	1.0	1.0	30		0.0				0.0												B364473	27.43	28.96	**0.213**			VA05074738	1.53
4	3	2.0	4.5	40		2.0	q/cb	3	3	0.1							0.1					B364474	28.96	30.48	**0.342**			VA05074738	1.52
2	4	0.4	0.7	70		30.0	q/cb	5	2	0.0																			
3	1	1.0	3.0	75	30	0.0				2.0								5.0				B364475	30.48	32.00	**0.346**			VA05074738	1.52
2	3	1.0	2.0	30		2.0	q/cb	4	5	2.0								5.0				B364476	BLANK		**<0.005**			VA05074738	
0																						B364477	32.00	33.53	**0.162**			VA05074738	1.53
2	1	1.0	1.5	65		1.0	q/cb	1	4	0.1								5.0				B364478	33.53	35.05	**0.067**			VA05074738	1.52
3	1	0.5	1.5	5		1.0	q/cb	5	5	0.1								5.0				B364479	35.05	36.58	**0.146**			VA05074738	1.53
1	3	1.5	1.5	35		5.0	c	4	4	1.0					1.0			5.0											
4	1	1.2	3.5	40		2.0	q/k	4	4	2.0			1.0					5.0	3.0			B364480	36.58	38.10	**0.161**			VA05074738	1.52
1	1	1.0	1.0	40		2.0	q/k	3	3	2.0			2.0					5.0	3.0			B364481	38.10	39.62	**0.060**			VA05074738	1.52
4	3	0.6	3.2	50		3.0	q/k/cb	4	4				5.0						4.0										
1	1	1.0	1.0	40		2.0	q/k	3	3	2.0			2.0					5.0	3.0			B364482	38.10	39.62	**0.107**	DUP		VA05074738	1.52
4	3	0.6	3.2	50		3.0	q/k/cb	4	4				5.0						4.0										
3	1	3.0	5.0	50		2.0	q/s	3	1	2.0			0.1					5.0	3.0			B364483	39.62	41.15	**0.126**			VA05074738	1.53
1	3	1.3	1.3	45		1.0	q/cb	4	4	0.1					0.1			5.0											
2	1	0.5	1.0	40		1.0	q/s	3	1	2.0	0.1		0.1					5.0	5.0	2.0		B364484	41.15	42.67	**0.154**			VA05074738	1.52
1	3	0.3	0.3	40		1.0	q/cb	2	2						0.1														
3	1	2.5	5.0	40	30	32.0	q/s	4	5	5.0			8.0					5.0	5.0			B364485	42.67	44.20	**0.656**		Ox'd zone	VA05074738	1.53
3	1	0.5	1.5	40	25	4.0	s/q/cb	3	3	2.0								5.0				B364486	44.20	45.72	**0.101**			VA05074738	1.52
3	1	1.0	2.0	50	90	3.0	q	3	4				2.0									B364487	45.72	47.24	**0.078**			VA05074738	1.52
3	1	1.0	2.0	40	50	2.0	q/cb	3	2				0.1		0.1							B364488	47.24	48.50	**0.208**			VA05074738	1.26
3	1	1.0	2.0	40	50	2.0	q/cb	3	2				0.1		0.1							B364489	47.24	48.50	**0.119**	PD/CA		VA05074738	1.26
																						B364490	STANDARD 6F		**2.530**	6F		VA05074738	
4	1	0.5	2.0	40		4.0	q/cb	2	3													B364491	48.50	49.60	**0.428**		>10% hem, broken up	VA05074738	1.10
2	1	1.0	2.0							0.0																			
2	1	1.0	2.0	50		2.0	q	2	2													B364492	49.60	50.29	**0.184**			VA05074738	0.69
3	1	1.0	2.0	40		4.0	q	2	4	0.1								5.0				B364493	50.29	51.82	**0.192**			VA05074738	1.53
5	1	1.0	3.5	50		4.0	q/k	3	4	0.1								5.0				B364494	51.82	53.34	**0.124**			VA05074738	1.52
6	1	1.0	4.5	40		3.0	q/k	3	4	0.1							2.0	5.0				B364495	53.34	54.86	**0.099**		Moly	VA05074738	1.52

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2005	PAGE 3 of 12	
DRILL HOLE # : DG05-303C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		64.01	74.68	GND: Highly oxidized section; Limonite throughout GND matrix; Five zones infused with carb-rich limonite, reduced to clay gouge material, no wider than 20cm each; Qtz/carb and qtz veins have silicified selvages up to 2cm wide, moderately oxidized to rusty brown.	4	1		2	3	
10		74.68	86.87	GND: No clay gouge zones; Competent, moderately to highly oxidized. One pure clay seam at 84.70m (8cm wide), carb rich, effervesces; Few 'clear' unoxidized GND zones up to 20cm long, within competent core; Within frequent quartz veins, very little mineralization, but more oxidized hematite (up to 10%), and often weathered out, leaving vugs along the center of the veins.	3	1		1	1	
10		86.87	97.54	GND: Unoxidized GND slightly more prevalent in zones up to 40cm wide; No clay seams but core is still very broken up - to gravel in 10cm intervals (3 zones, 10cm wide); Quartz and quartz-carb veins still frequent; Quartz veins have solid boundaries while carb-rich veins are more gradational. Sulphides (oxidized py, scor'd aspy) are rare.	2	1			2	
10		97.54	104.56	GND: Altered to aphanitic, more sericite present; Selvages difficult to distinguish; Core is ~40% solid, partially silicified; Still very broken up on limonite-covered planes at ~40° and 140° TCA; Veinlets of limonite have wide, visible brown selvages up to 12cm wide.	3	2			3	
10		104.56	108.20	GND: Same aphanitic GND but more highly oxidized and broken up into <5cm pieces over 90% of the section.	4	1		1	3	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B364496	BLANK		<0.005			VA05074738	
5	1	1.0	5.0	40		2.0	q/k/cb	3	4	0.1			4.0		1.0	0.1	5.0	1.0				B364497	54.86	56.39	0.075			VA05074738	1.53
2	3	1.0	1.5	60		8.0	q/cb	4	2				1.0				0.1		4.0										
2	1	0.6	0.9	30		3.0	q/cb	4	2				4.0		2.0							B364498	56.39	57.91	0.119			VA05074738	1.52
1	3	0.4	0.4	40		1.0	q/cb	4	1				5.0						3.0										
5	1	1.0	3.0	40	20	3.0	q/s	4	2		3.0		4.0				1.0		3.0			B364499	57.91	59.44	0.629			VA05074738	1.53
7	1	1.0	5.0	40	120	2.0	q/k/cb	4	3	0.1			0.1		1.0			5.0	1.0			B364500	59.44	60.96	0.215			VA05074738	1.52
3	3	0.3	0.9	35		2.0	q	3	2	0.1			4.0		0.1			5.0	4.0										
3	1	1.0	3.0	20		2.0	q	3	2	1.0			1.0					5.0				B364501	60.96	62.48	0.095			VA05074738	1.52
3	1	1.0	3.0	20		2.0	q	3	2	1.0			1.0					5.0				B364502	60.96	62.48	<0.005	DUP		VA05074738	1.52
5	1	2.0	5.5	40		3.0	q/cb/k	4	4	0.1			0.1					5.0	2.0			B364503	62.48	64.01	0.330			VA05074738	1.53
6	1	0.6	3.6	50	35	3.0	q/k.cb	3	4	0.1	1.0		3.0					5.0	1.0			B364504	64.01	65.53	0.122			VA05074738	1.52
4	1	2.0	4.5	50	60	0.0				0.1								5.0				B364505	65.53	67.06	0.281			VA05074738	1.53
4	1	1.0	4.0	40	60	2.0	q/k/cb	3	4	1.0								5.0				B364506	67.06	68.58	0.110			VA05074738	1.52
3	1	1.0	3.0	40		1.0	q	2	2	1.0								5.0				B364507	68.58	70.10	0.102			VA05074738	1.52
3	1	1.0	3.0	65		1.0	q/cb	3	2	2.0								5.0				B364508	70.10	71.63	0.062			VA05074738	1.53
1	3	0.5	0.5	40		1.0	q/cb	2	1				0.1						3.0										
3	1	1.0	3.0	65		1.0	q/cb	3	2	2.0								5.0				B364509	70.10	71.63	0.054	PD/CA		VA05074738	1.53
1	3	0.5	0.5	40		1.0	q/cb	2	1				0.1						3.0										
																						B364510	STANDARD 6F		2.660	6F		VA05074738	
2	1	0.6	1.2	40		1.0	q/cb	4	3	0.1								5.0				B364511	71.63	73.15	0.149			VA05074738	1.52
4	1	1.0	2.0	50	45	2.0	q/cb	4	2													B364512	73.15	74.68	0.294			VA05074738	1.53
4	1	1.0	4.0	50	35	2.0	q/cb	2	3	0.1					0.1			5.0				B364513	74.68	76.20	0.620			VA05074738	1.52
3	1	1.0	3.0	35		2.0	q/cb/s	3	3	2.0			4.0				0.1	5.0	4.0			B364514	76.20	77.72	0.992		Moly	VA05074738	1.52
4	1	2.0	5.0	35		2.0	q/s/cb	3	3	3.0			5.0				0.1	5.0	4.0			B364515	77.72	79.25	1.745			VA05074738	1.53
																						B364516	BLANK		<0.005			VA05074738	
5	1	1.5	4.5	30		1.0	q/cb	4	3	1.0								5.0				B364517	79.25	80.77	0.668			VA05074738	1.52
1	4	0.4	0.4	50		3.0	q/cb	2	4	5.0								5.0											
7	1	2.0	7.0	45		2.0	q/s/cb	3	3								1.0					B364518	80.77	82.30	0.734			VA05074738	1.53
5	1	1.3	4.5	20	45	3.0	q/s/cb	4	4	3.0								4.0				B364519	82.30	83.82	0.189			VA05074738	1.52
2	1	0.5	1.0	30		2.0	q	2	3	0.1								5.0				B364520	83.82	85.34	0.223			VA05074738	1.52
4	1	2.0	8.0	30		2.0	q/s/cb	4	3				5.0						4.0			B364521	85.34	86.87	0.424			VA05074738	1.53
4	1	2.0	8.0	30		2.0	q/s/cb	4	3				5.0						4.0			B364522	85.34	86.87	0.396	DUP		VA05074738	1.53
3	1	1.3	3.0	50		2.0	q	5	5	1.0								5.0				B364523	86.87	88.39	4.170			VA05074738	1.52
5	1	1.2	5.0	30	60	2.0	q/k	5	3	1.0					0.1			5.0				B364524	88.39	89.92	1.060			VA05074738	1.53
7	1	0.5	3.5	40	50	2.0	q/k/cb	4	4	3.0					0.1			5.0				B364525	89.92	91.44	0.149			VA05074738	1.52
4	1	0.5	2.0	50		2.0	q/k/cb	4	5	0.1								5.0				B364526	91.44	92.96	0.515			VA05074738	1.52
1	1	1.0	1.0	40		3.0	q/cb	4	3													B364527	92.96	94.49	1.415			VA05074738	1.53
4	3	0.4	2.4	40		2.0	q/s/cb	3	1				5.0						4.0										
1	1	0.5	0.5	40		6.0	q/s/cb	3	4						0.1							B364528	94.49	96.01	0.068			VA05074738	1.52
1	3	0.5	0.5	30		2.0	q/cb	2	5	0.1					0.1			5.0											
1	1	0.5	0.5	40		6.0	q/s/cb	3	4						0.1							B364529	94.49	96.01	0.080	PD/CA		VA05074738	1.52
1	3	0.5	0.5	30		2.0	q/cb	2	5	0.1					0.1			5.0											
																						B364530	STANDARD 4D		0.454	4D		VA05074738	
1	1	0.6	0.6	30		2.0	q/s/cb	4	3	0.1					0.1			5.0				B364531	96.01	97.54	0.037			VA05074738	1.53
1	1	2.0	2.0	30						0.1								5.0				B364532	97.54	99.06	0.187			VA05074738	1.52
3	1	2.0	2.8	40		10.0	q	3	2	2.0								5.0				B364533	99.06	100.58	4.310			VA05074738	1.52
1	4	0.4	0.4	50		6.0	q/s/cb	2	3													B364534	100.58	101.66	0.073			VA05074738	1.08
0																						B364535	101.66	103.12	0.254			VA05074738	1.46
																						B364536	BLANK		<0.005			VA05074738	
0																						B364537	103.12	104.56	0.167			VA05078597	1.44
0																						B364538	104.56	106.13	0.327			VA05078597	1.57
0																						B364539	106.13	106.88	0.082			VA05078597	0.75
0																						B364540	106.88	108.20	0.132			VA05078597	1.32

DRILL LOG LEGEND P1	DATE: August 5 - 20, 2005	PAGE 6 of 12		
DRILL HOLE # : DG05-303C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence	

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		108.20	112.78	GND: Same aphanitic GND, silicified and almost completely oxidized, although 100% of section is competent; As for veins, only a few small ones are visible; Oxidized hematite (and pyrite?) seen disseminated through section, so perhaps qtz veins contributed to silicification and were incorporated into GND.	3	2			1	
10		112.78	118.87	GND: Same aphanitic GND; More altered and sheared and broken up, especially from 113.65m to 114.6m, where shear and sericite is intense; Also at 118.55m a 15cm zone of fault breccia; Jointing at 25° and 100° TCA.	3	3		1	3	
10		118.87	132.59	GND: Unaltered GND (50%) with quartz veins with oxidized and/or silicified selvages (50%); Decreased limonite; 80% competent core (pieces >10cm); Common sheeted veins; Sulphides within (py, po, aspy) are oxidized up to 100% at least 50%; Molybdenite appears as soft, bluish-silver, rounded pieces within or beside quartz veins; Quartz veins have clear boundaries and obvious selvages, mostly silicified within sericite alteration as well, often limonitic.	2	1			1	
10		132.59	139.78	GND with numerous 1mm-1cm quartz veins; Selvages up to 10cm, are silicified and sericitic usually with rusty oxidation and carbonate.	2	2		1	2	
10		139.78	140.83	All oxidized and sericitized; GND texture 90% reduced to aphanitic. One quartz vein with strongly-defined selvage.	4	3			2	
		140.83	144.78	GND: Big, frequent quartz veins with oxidized selvages; Limonite still on fracture planes and throughout GND matrix; Slickensides in sericite on low angle fracture faces	3	1			3	
10		144.78	146.86	GND: Completely oxidized and broken up to coarse gravel/sand-size fragments; Colour is pale to medium brown; No competent core but gravel chunks appear as highly sericitized GND or quartz eyes.	5	3		3	4	
10		146.86	159.43	GND: Competent core with a lot less limonite, only thinly distributed along veinlets/fracture faces. Milky white to pale grey quartz veins with ox'd, ser'd, silicified selvages. Minor sulphides are mostly oxidized. Beginning around 150m (+/- 20cm), alteration is more pervasive and GND texture reduced to aphanitic with only qtz eyes preserved (20% rounded, 2mm grains), Other 80% is oxidized/limonite-stained and/or sericitized to pale green; From 152.0 - 156.0m rock is 70% competent and has ~5-10 cm bands of different alteration types; These bands are oriented at ~20°-50° TCA; Sericite, clay rich and oxidized competent GND make up this section. Colourful; First view unaltered GND at 156.0m; Still has branching veinlets of limonite throughout, crumbly brecciated gouge at 156.85m for 15cm; 2 more before 159.43m.	4	3	1	2	4	
10		159.43	161.79	GND: Zone of extreme alteration but minimal oxidation; Remnant bt texture and qtz preserved from original GND, but 90% texture is massive and speckled with oxidized carbonate, up to 3mm in diameter; Veins are relicts, bent, with little to no selvage.	2	5	2	1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 5 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scorodite	biotite	other		From	To					
1	1	0.3	0.3	40		1.0	q/cb	3	2													B364541	108.20	109.73	0.070			VA05078597	1.53
1	1	0.3	0.3	40		1.0	q/cb	3	2													B364542	108.20	109.73	0.067	DUP		VA05078597	1.53
3	1	0.3	0.9	40		1.0	q/cb	3	3	0.1								5.0	2.0			B364543	109.73	111.25	0.107			VA05078597	1.52
1	1	0.3	0.3	40		2.0	q/s	4	1				1.0						4.0			B364544	111.25	112.78	0.707			VA05078597	1.53
1	1	0.3	0.3	40		1.0	q/cb	5	2				0.1									B364545	112.78	114.30	0.160			VA05078597	1.52
1	1	0.7	0.7	35		4.0	q/cb/s	3	2	0.1			0.1					5.0	5.0			B364546	114.30	115.82	0.416			VA05078597	1.52
2	1	1.0	1.5	40		8.0	q/s	4	2								0.1					B364547	115.82	117.35	0.056		Moly	VA05078597	1.53
5	1	1.5	4.5	35		4.0	q/cb/s	2	2								0.1					B364548	117.35	118.87	6.500			VA05078597	1.52
5	1	1.5	4.5	35		4.0	q/cb/s	2	2								0.1					B364549	117.35	118.87	4.670	PD/CA		VA05078597	1.52
																						B364550	STANDARD 3C		0.096	3C		VA05078597	
5	1	1.0	5.0	50		4.0	q/cb/s	4	2				3.0						2.0			B364551	118.87	120.40	0.706			VA05078597	1.53
5	1	1.0	4.0	50		4.0	q/cb/s	4	2	0.1								5.0				B364552	120.40	121.92	1.495			VA05078597	1.52
6	1	1.0	5.0	50		2.0	q/cb/s	4	3	1.0			1.0					5.0	2.0			B364553	121.92	123.44	0.749			VA05078597	1.52
7	1	1.0	4.5	40		4.0	q/s	3	1	0.1	2.0		0.1					1.0	3.0			B364554	123.44	124.97	5.330			VA05078597	1.53
4	1	1.0	3.0	30		3.0	q/cb/k	2	1	0.1	3.0		0.1					1.0	3.0			B364555	124.97	126.49	1.260			VA05078597	1.52
3	3	0.3	0.9	30		2.0	s/cb	2	1																				
																						B364556	BLANK		<0.005			VA05078597	
3	1	1.0	3.0	50		2.0	q/s	4	1	2.0								2.0				B364557	126.49	128.02	0.226			VA05078597	1.53
7	1	1.0	5.5	40	50	2.0	q/cb	4	2	1.0							3.0	1.0	4.0			B364558	128.02	129.54	2.330		Scor, moly, ox py	VA05078597	1.52
2	1	1.0	1.5	45		2.0	q/s	4	1	2.0					0.1		1.0	2.0				B364559	129.54	131.06	0.152			VA05078597	1.52
7	3	0.3	2.1	40		1.0	q/cb	3	1																				
6	1	1.0	5.0	40		4.0	q/s	5	1										3.0			B364560	131.06	132.59	0.946			VA05078597	1.53
3	1	1.0	3.0	30	60	1.0	q/cb	3	2	1.0								1.0				B364561	132.59	134.11	4.640			VA05078597	1.52
3	1	1.0	3.0	30	60	1.0	q/cb	3	2	1.0								1.0				B364562	132.59	134.11	9.050	DUP		VA05078597	1.52
6	1	2.0	6.5	45	30	10.0	q/cb	4	4	1.0							0.1	1.0				B364563	134.11	135.64	1.350		moly	VA05078597	1.53
5	1	1.0	3.5	40		2.0	q/s/cb	3	2	0.1			4.0		0.1			5.0	4.0			B364564	135.64	137.16	1.250			VA05078597	1.52
5	1	1.0	4.0	35		6.0	q/s/cb	3	1	0.1	3.0							5.0				B364565	137.16	138.68	0.608		Cu coloured po	VA05078597	1.52
1	3	0.3	0.3	40		2.0	q/cb/s	3	0	0.1	q																		
3	1	1.0	3.0	40		4.0	q/s	3	2	1.0					2.0			5.0	5.0			B364566	138.68	139.78	0.650			VA05078597	1.10
1	3	0.3	0.3	55		1.0	cb	2	3																				
1	1	1.0	1.0	40		3.0	q/cb	5	3	0.1							0.1	5.0				B364567	139.78	140.83	0.909			VA05078597	1.05
5	1	1.0	3.0	40		3.0	q/s	3	1		2.0							5.0				B364568	140.83	141.73	0.544			VA05078597	0.90
5	1	1.0	3.0	40		3.0	q/s	3	1		2.0							5.0				B364569	140.83	141.73	1.330	PD/CA		VA05078597	0.90
																						B364570	STANDARD 1A		1.015	1A		VA05078597	
8	1	1.0	5.0	40		4.0	q/cb	4	2	1.0	2.0				0.1			5.0				B364571	141.73	143.26	2.740			VA05078597	1.53
6	1	2.5	9.0	40	20	2.0	cb/q	3	3				2.0						5.0			B364572	143.26	144.78	1.115			VA05078597	1.52
1	3	2.0	2.0	30		2.0	cb/q	3	3				4.0						5.0										
0																						B364573	144.78	145.80	1.415			VA05078597	1.02
0																						B364574	145.80	146.86	0.672			VA05078597	1.06
5	1	1.3	5.0	30	15	8.0	q/s	5	1	2.0	2.0		3.0					3.0				B364575	146.86	147.83	1.025			VA05078597	0.97
																						B364576	BLANK		<0.005			VA05078597	
6	1	1.5	5.5	60	25	4.0	q/cb/s	4	2	1.0								5.0				B364577	147.83	149.35	0.946			VA05078597	1.52
3	1	1.0	3.0	30		2.0	q/cb/s	2	4	0.1								5.0				B364578	149.35	150.88	1.165			VA05078597	1.53
1	3	0.5	0.5	40		2.0	q/cb/s	3	4	1.0								5.0											
4	1	2.0	5.3	35	10	10.0	q/s/cb	4	4	2.0			1.0					0.0	0.0			B364579	150.88	152.40	2.900			VA05078597	1.52
7	1	0.5	3.5	50		4.0	q/cb/s	5	5	0.1								5.0				B364580	152.40	153.92	1.360			VA05078597	1.52
4	1	2.0	5.0	65		4.0	q/cb/s	5	3		2.0						0.1					B364581	153.92	155.45	0.669			VA05078597	1.53

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2005 PAGE 7 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.79	165.27	GND: Same sericitized GND except highly oxidized as well; Limonite throughout, so rock is broken up into gravel in 2 zones: 30cm at 163.9m and 15cm at 164.8m; At 162.75m - 163.0m, banding of greenish dark grey clay with white carbonate in between, at 80° TCA; Overall color is strong orangey brown masking bluish green micaceous rock.	5	5	1	2	4	
10		165.27	170.39	GND: GND texture visible over 75% of section, not oxidized and minor alteration; Rock is weakened by influx of carbonate and sericite (no veins associated) at 167.5 - 167.64m; Last 50cm is all rearranged and alt'd GND, surrounding relict quartz vein.	2	2	1	1	2	
10		170.39	195.07	GND: Large zone of silicified and sericitized GND; Texture is cryptocrystalline except for ~10% (secondary?) biotite, up to 2mm in diameter; Frequent qtz, carb and qtz/carb veins produce carb-rich selvages which appear as lighter green than the surrounding deep blue-green rock matrix; The whole section is silicified, so is probably a selvage of the sheeted veins itself, but cannot be separated between veins here; Selvages are carb'd, ser'd and sil'd; Super carb-rich zone at 175.26 - 175.50m; Softened and broken into <10cm pieces; From 189.55 - 195.07m is all "selvage", carb-rich and weakened GND, no more silicified deep blue-green.	1	5	2	1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 6 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval					
										Sulphides								Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	3	1.0	1.0	65		6.0	s/cb	5	3	2.0								5.0											
4	1	2.0	5.0	65		4.0	q/cb/s	5	3		2.0						0.1					B364582	153.92	155.45	**0.698**	DUP		VA05078597	1.53
1	3	1.0	1.0	65		6.0	s/cb	5	3	2.0								5.0											
2	1	4.0	6.0	65	30	20.0	q/s/cg/chl	5	2	10.0								3.0				B364583	155.45	156.97	**1.165**			VA05078597	1.52
2	1	0.6	1.2	40		4.0	q/cb/s	3	4	0.1				0.1			0.1	4.0				B364584	156.97	158.50	**0.399**			VA05078597	1.53
2	1	2.0	4.0	70		2.0	q/cb/s	4	3	4.0								5.0				B364585	158.50	159.43	**1.175**			VA05078597	0.93
2	1	1.0	2.0	40		2.0	q	2	0													B364586	159.43	160.61	**0.094**			VA05078597	1.18
2	1	1.0	2.0	50		0.0				0.1								5.0				B364587	160.61	161.79	**0.983**			VA05078597	1.18
0																						B364588	161.79	163.07	**0.079**			VA05078597	1.28
0																						B364589	161.79	163.07	**0.086**	PD/CA		VA05078597	1.28
																						B364590	STANDARD 4D		**0.460**	4D		VA05078597	
1	1	2.0	2.0			0.0				0.0												B364591	163.07	164.59	**1.650**		Quartz piece <1cm in diam	VA05078597	1.52
0																						B364592	164.59	165.27	**0.354**			VA05078597	0.68
0																						B364593	165.27	166.12	**0.036**			VA05078597	0.85
3	1	3.0	6.0	45		2.0	q	2	2				1.0		2.0		0.1		2.0			B364594	166.12	167.64	**0.325**		moly	VA05078597	1.52
4	1	2.5	6.0	50	40	1.0	q	4	0		20.0											B364595	167.64	169.16	**0.632**			VA05078597	1.52
1	6	0.4	0.4	50		1.0	cb/q	5	0		70.0		10.0						5.0										
																						B364596	BLANK		**<0.005**			VA05078597	
3	1	1.0	3.0	40		0.0																B364597	169.16	170.39	**0.135**			VA05078597	1.23
1	1	2.0	2.0	40		50.0	q/cb/chl	5	2	5.0								5.0											
6	1	2.0	7.0	60	50	8.0	cb/s/chl	4	1	3.0								2.0				B364598	170.39	171.30	**0.453**			VA05078597	0.91
2	1	1.5	2.2	50	70	4.0	cb/s	4	0	0.1								5.0				B364599	171.30	172.21	**0.234**			VA05078597	0.91
2	3	0.5	1.0	45		4.0	cb/s/chl	4	0																				
2	1	2.5	3.5	50	70	40.0	cb/s	5	1	5.0								5.0				B364600	172.21	173.74	**0.090**			VA05078597	1.53
2	1	4.0	8.0	80		40.0	cb/s	5	5	4.0								4.0				B364601	173.74	175.26	**0.350**			VA05078597	1.52
2	1	4.0	8.0	80		40.0	cb/s	5	5	4.0								4.0				B364602	173.74	175.26	**1.455**	DUP		VA05078597	1.52
5	1	6.0	16.0	70		4.0	cb/s	5	1		3.0		1.0									B364603	175.26	176.78	**0.526**			VA05078597	1.52
4	1	2.5	6.0	50		4.0	cb/s	5	0	5.0	2.0							3.0				B364604	176.78	178.31	**2.390**			VA05078597	1.53
1	4	0.5	0.5	45		40.0	cb/q	5	0																				
5	1	4.0	8.5	55		8.0	cb/s/chl	5	1	2.0	3.0		0.1									B364605	178.31	179.83	**2.880**			VA05078597	1.52
1	6	0.5	0.5	40		1.0	cb/q	4	1		40.0	10.0	20.0					4.0											
7	1	8.0	14.0	50		50.0	cb/s/chl	5	0	3.0								3.0				B364606	179.83	181.36	**0.723**			VA05078597	1.53
2	1	0.8	1.5	50	70	4.0	cb/s	5	0	0.1	2.0							4.0				B364607	181.36	182.88	**0.058**			VA05078597	1.52
4	4	0.3	1.2	50	15	1.0	cb	2	0																				
6	1	1.0	4.7	50		22.0	cb/s	5	0		1.0											B364608	182.88	184.40	**0.945**			VA05078597	1.52
2	4	0.3	0.6	50		4.0	cb/s	5	0																				
6	1	1.0	4.7	50		22.0	cb/s	5	0		1.0											B364609	182.88	184.40	**0.761**	PD/CA		VA05078597	1.52
2	4	0.3	0.6	50		4.0	cb/s	5	0																				
																						B364610	STANDARD 7G		**4.290**	7G		VA05078597	
2	1	1.2	2.0	50		4.0	cb/s	5	2													B364611	184.40	185.93	**3.220**		Low angle vein selvage width of core.	VA05078597	1.53
1	6	0.3	0.3	0	10		cb	5	2	100.0								5.0											
3	1	1.2	3.3	50		2.0	cb/s	5	0	0.1								5.0				B364612	185.93	187.45	**0.202**			VA05078597	1.52
5	1	3.0	8.5	60	50	8.0	cb/s	5	0	0.1								5.0				B364613	187.45	188.98	**1.680**			VA05078597	1.53
2	4	0.6	0.4	60	50	8.0	cb/s	5	0																				
3	1	3.0	5.0	60	50	20.0	cb/s	5	0	2.0								2.0				B364614	188.98	190.50	**1.645**			VA05078597	1.52
5	1	5.0	7.5	40		40.0	cb/s	5	1	0.1								5.0				B364615	190.50	192.02	**0.240**			VA05078597	1.52
																						B364616	BLANK		**<0.005**			VA05078597	
4	1	2.0	5.0							0.1												B364617	192.02	193.55	**1.140**			VA05078597	1.53
1	6	1.0	1.0	25		10.0	cb/chl/s	5	1	100.0								5.0											
2	1	1.0	2.0	60						0.1								5.0				B364618	193.55	195.07	**7.410**			VA05078597	1.52
2	4	0.4	0.8	60		0.0																							
2	6	1.0	1.5	50		10.0	cb/chl/s	5		100.0								5.0											

DRILL LOG LEGEND P1	DATE: August 5 - 20, 2005	PAGE 9 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		195.07	204.22	GND: From 195.07 - 196.6m is a gradation from sericitized and silicified GND to unalt'd GND between veins. After this, veins are similarly frequent and have carb/ser selvages but are separated by less alt'd GND instead of deep blue-green silicified; This "less altered" GND has minor sericite alteration, such that texture is 80% preserved, outside of selvages, but rock is still sericite-rich; Slickensides at 200m.	1	4		1	3	
10		204.22	208.79	GND: Carb-rich GND, weakened and broken up, especially from 205.74-208.5m (middle of section); Pieces ≤10cm long, not full core diameter. In this zone as well are slickensides in fresh pyrite and sericite, on low angle fractures, 20° TCA, slickensides to 80°.	2	4	1	2	4	
10		208.79	217.93	GND: Carb still prevalent but not as much as above; Numerous large quartz veins (up to 7cm) with sulphides both within and concentrated at boundaries of veins; Larger and stronger selvage alteration associated with increased sulphide content in/beside veins; At 220m, a 6cm quartz vein is at 5° TCA, so is seen across ~1m interval; Sulphides are minimal (~2% po and trace ox'd py); Bt alt'n within, 5%.	2	4	1	1	2	
10		217.93	228.60	GND: Unaltered GND with slightly fewer and smaller quartz veins with well-defined selvages; Veins in 2 orientations (0-5° and 50-60°) appear to be coeval, or high angle offset low angle veins, slightly		2	1		2	
10		228.60	243.84	GND: More weakened by carb veinlets in random orientations, so broken up to crumbly in spots up to 30cm long; Between 241.0 and 242.6m, low angle quartz veins contain a high concentration of carbonate and chlorite (up to 50%).		2	1	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 6 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval					
										Sulphides									Oxidation									
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
2	1	0.5	1.0	60		1.0	q	3	0		3.0											B364619	195.07	196.60	**0.166**			VA05078597	1.53
3	1	2.5	5.5	60	50	10.0	cb/s	5	0		2.0											B364620	196.60	198.12	**0.070**			VA05078597	1.52
3	3	1.0	3.0	60		8.0	c/s	5	0																			
6	1	2.0	7.0	65	30	10.0	cb/s	4	0	6.0	4.0		1.0					4.0				B364621	198.12	199.64	**0.093**			VA05080698	1.52
6	1	2.0	7.0	65	30	10.0	cb/s	4	0	6.0	4.0		1.0					4.0				B364622	198.12	199.64	**0.152**	DUP		VA05080698	1.52
6	1	1.5	6.0	50	70	10.0	cb/s	4	1	4.0	3.0											B364623	199.64	201.17	**0.203**			VA05080698	1.53
6	1	2.0	9.0	40	75	20.0	cb/s	5	0	1.0								5.0				B364624	201.17	202.69	**0.175**			VA05080698	1.52
7	1	1.2	5.0	30	40	6.0	cb/s	5	1	1.0								5.0				B364625	202.69	204.22	**0.696**			VA05080698	1.53
1	4	0.4	0.4	45		24.0	cb/s	5	0	5.0								5.0											
3	1	3.0	9.0	30	15	20.0	cb/s	5	1	8.0								4.0				B364626	204.22	205.74	**0.256**			VA05080698	1.52
1	6	0.6	0.6	75		2.0	cb	5	3	100.0								5.0											
2	4	0.5	1.0	30		8.0	s/cb	5	2																				
4	1	2.0	4.5	55		24.0	s/cb	5	1	4.0								3.0				B364627	205.74	207.26	**0.078**		Slicks in fresh pyrite	VA05080698	1.52
5	1	4.0	15.0	55	15	30.0	cb/s	5	2	4.0	3.0							5.0				B364628	207.26	208.79	**0.391**			VA05080698	1.53
5	1	4.0	15.0	55	15	30.0	cb/s	5	2	4.0	3.0							5.0				B364629	207.26	208.79	**0.333**	PD/CA		VA05080698	1.53
																						B364630	STANDARD 5E		**1.485**	5E		VA05080698	
5	1	2.0	6.0	50	35	8.0	cb/s	5	0	2.0	4.0							4.0				B364631	208.79	210.31	**0.062**		Ox'd pyrite along margins	VA05080698	1.52
2	4	0.3	0.6	45		4.0	cb/s/q	5		10.0								5.0											
5	1	7.0	10.0	65	35	40.0	cb/s/q	5	1	12.0								3.0				B364632	210.31	211.84	**0.327**			VA05080698	1.53
7	1	1.0	6.5	50	40	8.0	cb/s	5	0	3.0	5.0							5.0				B364633	211.84	213.36	**0.243**			VA05080698	1.52
3	1	2.0	3.5	60		10.0	cb/s	5	1	2.0								3.0				B364634	213.36	214.12	**0.197**			VA05080698	0.76
3	1	7.0	10.0	60	80	20.0	cb/s	5	1	15.0								3.0				B364635	214.12	214.88	**0.647**			VA05080698	0.76
																						B364636	BLANK		**<0.005**			VA05080698	
1	6	8.0	8.0	60							100.0							5.0				B364637	214.88	216.41	**0.430**			VA05080698	1.53
5	1	3.0	10.0	55	35	6.0	cb/s	3	0	2.0	3.0		2.0					5.0											
6	1	1.0	5.0	45	60	1.0	q/s	3	0		2.0											B364638	216.41	217.93	**0.245**			VA05080698	1.52
2	3	0.5	1.0	50		2.0	cb/s/q	4	1	0.1			0.1					5.0											
7	1	2.0	9.0	20	40	2.0	cb/q/s	3	0	0.1	2.0							5.0	5.0			B364639	217.93	219.46	**0.303**			VA05080698	1.53
3	1	6.0	9.0	40	5	2.0	s/q	5	0	1.0	2.0							5.0		5.0		B364640	219.46	220.98	**0.673**		Unaltered po	VA05080698	1.52
7	1	10.0	24.0	25	50	3.0	q/s/cb	4	0	2.0	5.0	0.1						1.0				B364641	220.98	222.50	**0.470**			VA05080698	1.52
7	1	10.0	24.0	25	50	3.0	q/s/cb	4	0	2.0	5.0	0.1						1.0				B364642	222.50	222.50	**0.096**	DUP		VA05080698	0.00
6	1	3.0	7.5	50	5	3.0	cb/s	4			2.0								5.0	3.0		B364643	222.50	224.03	**0.197**			VA05080698	1.53
6	1	1.2	4.0	50		4.0	cb/s/chl	4	0		4.0								5.0			B364644	224.03	225.55	**0.526**			VA05080698	1.52
7	1	1.0	4.0	55	30	2.0	cb/q/s	4			8.0								3.0	2.0		B364645	225.55	227.08	**0.087**			VA05080698	1.53
6	1	1.0	5.0	70	20	10.0	s/chl/cb	5	0	3.0	0.1							5.0		0.1		B364646	227.08	228.60	**0.431**			VA05080698	1.52
4	1	1.0	3.5	40		1.0	cb/q/s	2	0		2.0								2.0	2.0		B364647	228.60	230.12	**0.223**			VA05080698	1.52
4	1	1.5	4.5	50	70	1.0	q	3	1		6.0								5.0	4.0		B364648	230.12	231.65	**0.122**			VA05080698	1.53
1	3	0.5	0.5	45		2.0	q/cb	3	0		10.0																		
4	1	1.5	4.5	50	70	1.0	q	3	1		6.0								5.0	4.0		B364649	230.12	231.65	**0.108**	PD/CA		VA05080698	1.53
1	3	0.5	0.5	45		2.0	q/cb	3	0		10.0																		
																						B364650	STANDARD 2B		**3.040**	2B		VA05080698	
4	1	3.0	5.5	60	20	4.0	cb/s/q	4	0		3.0	0.1								1.0		B364651	231.65	233.17	**0.493**			VA05080698	1.52
1	4	1.0	1.0	45		6.0	cb/s/q	3	0		10.0																		
3	1	1.0	3.0	50		4.0	cb/s/chl/q	4			5.0		5.0						5.0	2.0		B364652	233.17	234.70	**0.215**			VA05080698	1.53
2	4	0.3	0.6	35	0	0.5	cb	4																					
5	1	3.0	6.5	30	60	2.0	q/cb/chl	4	0	2.0	0.1							5.0	2.0			B364653	234.70	236.22	**0.856**			VA05080698	1.52
5	3	0.3	1.5	45		2.0	cb/chl	5	0		0.1								2.0										
6	1	4.0	11.0	60	45	10.0	s/chl/cb	5	0	1.0	10.0	0.1	2.0									B364654	236.22	237.74	**0.940**			VA05080698	1.52
2	4	0.2	0.4	60		4.0	cb/s	4			4.0		2.0																
2	1	1.2	2.2	60		2.0	q/chl	4	0		10.0											B364655	237.74	239.27	**0.180**			VA05080698	1.53
2	4	1.0	2.0	30	15	2.0	cb	3	1																				
																						B364656	BLANK		**<0.005**			VA05080698	
2	1	1.5	2.7	50		0.5	q/cb	4	0		3.0		6.0									B364657	239.27	240.79	**0.509**			VA05080698	1.52

DRILL LOG LEGEND P1	DATE: August 6 - 20, 2006 PAGE 11 of 12	
DRILL HOLE # : **DG05-303C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		243.84	259.08	GND: 95% unalt'd GND; Few quartz veins have <5cm selvages; Sericite, chlorite and silicification alteration moderate within; Competent core except where moderate carbonate intrudes on veinlets at random angles TCA: from 246.89m - 247.07m and 242.9 - 243.0m. This section contains two types of quartz veins with the same mineralization (~5% po); Thin (0.5cm) veins at 50-60° TCA with 2-3cm selvages, and 1.5-2cm veins with little or no selvages, generally at 50° TCA; Each section usually contains 1 wide one and 3-4 of the smaller type.		1	1		1	
10		259.08	271.27	GND: Somewhat more alt'd and broken up core; Evidence of movement from 259.5 - 260.0m; Carb, chl and ser rich zone and one qtz vein moved 1cm, sinistrally; Other than these zones of alt'n, rock is unaltered GND with ~2-3 carb-rich qtz veins per metre.	1	2	2		2	
10		271.27	280.42	GND: Moderate carb influx weakens otherwise unalt'd GND; 4-6 quartz veins per metre. Whole section is crumbly and broken up; Carb veinlets at low angles TCA cause breakage.		3	2	1	3	
10		280.42	292.61	Unalt'd, competent GND. 5mm to 2cm qtz veins still frequent: ~5 veins per metre.Three zones of sericitic/chloritic/minor carb alt'n: from 285.40-286.10m, from 286.8-286.9m, and from 287.50-288.04m. Last sample contains 2 types of qtz veins - one 3cm vein contains sulphides, one does not.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 6 - 10, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	3	1.0	2.0	0	15	26.0	cb	3			15.0								10.0			B364658	240.79	242.32	**3.620**			VA05080698	1.53
1	1	5.0	5.0	30		40.0	cb/s	3			5.0								5.0										
6	1	25.0	6.0	45	15	1.0	cb/s	3	1	5.0	4.0							5.0				B364659	242.32	243.84	**1.225**			VA05080698	1.52
4	1	1.0	3.0	50		4.0	chl/q	4	0		5.0		0.1									B364660	243.84	245.36	**0.124**			VA05080698	1.52
5	1	2.0	5.5	50		4.0	cb/chl	5	0	0.1	2.0		0.1									B364661	245.36	246.89	**0.049**			VA05080698	1.53
5	1	2.0	5.5	50		4.0	cb/chl	5	0	0.1	2.0		0.1									B364662	245.36	246.89	**0.098**	DUP		VA05080698	1.53
4	1	1.0	1.8	50	40	3.0	cb/s	4	0		5.0		0.1						4.0			B364663	246.89	248.41	**0.276**			VA05080698	1.52
5	1	2.0	4.5	50	60	1.0	q/cb	3	0		5.0											B364664	248.41	249.94	**0.079**			VA05080698	1.53
6	1	1.5	5.0	50	60	2.0	s/chl	3	0		5.0	0.1	1.0						1.0			B364665	249.94	251.46	**0.058**			VA05080698	1.52
3	1	0.8	2.0	40	20	1.0	q/cb	2	0		5.0		0.1						5.0			B364666	251.46	252.98	**0.152**			VA05080698	1.52
4	1	1.5	2.5	50		2.0	q/cb/chl	3	0		5.0		0.1						3.0			B364667	252.98	254.51	**2.150**			VA05080698	1.53
2	3	0.2	0.4	50		2.0	cb/chl	2	0																				
3	1	4.3	5.5	45	60	2.0	cb/s	3	0		5.0	0.1										B364668	254.51	256.03	**1.610**			VA05080698	1.52
3	1	4.3	5.5	45	60	2.0	cb/s	3	0		5.0	0.1										B364669	254.51	256.03	**1.195**	PD/CA		VA05080698	1.52
																						B364670	STANDARD 7G		**4.520**	7G		VA05080698	
3	1	1.0	2.3	60	20	10.0	cb/chl	3	0		4.0		0.1						5.0			B364671	256.03	257.56	**0.606**		Po in selvage	VA05080698	1.53
1	1	9.0	9.0	55		7.0	s/chl	4	0		3.0											B364672	257.56	259.08	**2.600**			VA05080698	1.52
3	1	1.5	3.5	50	70	20.0	chl/cb/q	5		0.1								5.0				B364673	259.08	260.60	**0.737**			VA05080698	1.52
2	1	1.0	2.0	50		2.0	q/chl	2	0		0.1											B364674	260.60	262.13	**0.187**			VA05080698	1.53
2	3	1.0	2.0	60		2.0	q/cb/chl	4	0		2.0																		
2	1	1.1	2.0	60		2.0	cb/q	5	0		3.0								5.0			B364675	262.13	263.65	**0.108**			VA05080698	1.52
																						B364676	BLANK		**<0.005**			VA05080698	
2	1	0.5	1.0	55		4.0	cb/q/s	4			10.0											B364677	263.65	265.18	**0.227**			VA05080698	1.53
1	3	8.0	8.0	40		60.0	cb/chl/s	5		5.0								5.0											
2	3	0.5	1.0	60		20.0	cb/s	4		0.1								5.0				B364678	265.18	266.70	**0.157**			VA05080698	1.52
4	1	1.0	4.0	50		4.0	q/chl	3	0		6.0											B364679	266.70	268.22	**0.201**			VA05080698	1.52
4	1	0.4	1.6	60	40	2.0	cb/q/s	4	0		3.0											B364680	268.22	269.75	**0.232**			VA05080698	1.53
3	1	0.5	1.3	60	80	1.0	q/chl	3			10.0											B364681	269.75	271.27	**0.164**			VA05080698	1.52
3	1	0.5	1.3	60	80	1.0	q/chl	3			10.0											B364682	269.75	271.27	**0.143**	DUP		VA05080698	1.52
5	1	2.0	6.5	50		4.0	q/cb/s	4	0		10.0		1.0									B364683	271.27	272.80	**0.736**		"clean" aspy	VA05080698	1.53
6	1	2.5	8.5	40	130	1.0	q/cb/s	4	0		10.0											B364684	272.80	274.32	**0.694**			VA05080698	1.52
5	1	6.0	8.0	50		0.5	q	4			6.0											B364685	274.32	275.84	**0.112**			VA05080698	1.52
5	1	2.0	6.0	30	60	3.0	q/chl	3		1.0	8.0						0.1					B364686	275.84	277.37	**1.145**		Moly	VA05080698	1.53
6	1	1.3	6.0	50	30	2.0	q/chl	4	0		14.0		0.1						4.0			B364687	277.37	278.89	**0.119**			VA05080698	1.52
3	1	1.0	2.0	50		1.0	q	3			2.0								4.0			B364688	278.89	280.42	**0.226**			VA05080698	1.53
1	3	1.2	1.2	60		3.0	q/s	3			2.0																		
3	1	1.0	2.0	50		1.0	q	3			2.0								4.0			B364689	278.89	280.42	**0.305**	PD/CA		VA05080698	1.53
1	3	1.2	1.2	60		3.0	q/s	3			2.0																		
																						B364690	STANDARD 5E		**1.445**	5E		VA05080698	
4	1	1.2	2.2	40	55	1.0	q/s	3			5.0											B364691	280.42	281.94	**0.303**			VA05080698	1.52
4	1	0.5	2.0	40		1.0	q/s	2			9.0								2.0			B364692	281.94	283.46	**0.232**			VA05080698	1.52
7	1	1.4	5.0	40	50	1.0	q/s	3			2.0									4.0		B364693	283.46	284.99	**0.378**			VA05080698	1.53
4	1	1.0	4.0	60		1.0	q/s	4	0		7.0											B364694	284.99	286.51	**0.051**			VA05080698	1.52
2	3	1.0	2.0	30		50.0	cb/s/chl	4																					
4	1	1.0	3.5	60		4.0	cb/s/chl	4			4.0											B364695	286.51	288.04	**0.517**			VA05080698	1.53
																						B364696	BLANK		**<0.005**			VA05080698	
7	1	1.0	5.0	60		2.0	q/chl	3	0		5.0											B364697	288.04	289.56	**0.282**			VA05080698	1.52
4	1	1.5	3.0	60	30	1.0	q/s	3	0		2.0											B364698	289.56	291.08	**0.384**			VA05080698	1.52
3	1	3.0	5.0	65		2.0	cb/s	4		1.0	4.0		2.0									B364699	291.08	292.61	**0.168**			VA05080698	1.53
1	1	3.0	3.0	60		8.0	cb/q/s	4											6.0										
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-304C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1179m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 5-10, 2005 | DATES LOGGING: Aug 28 - Sept 1, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 460054 NORTHING: 7099197

COORD SYSTEM: NAD 83: EASTING: 459935 NORTHING: 7099383

NAD 27 (CORRECTED for historic grid): EASTING: 460024 NORTHING: 7099207

SECTION LINE(historic grid)

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 5.79m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B364053 - B364180

Requisition #: MASP448STRGOL.05Q Date Shipped: 6-Sept-05

Lab Record #: VA05080930 Date Received: 20-Sept-05

Sample Sequence: B364181 - B364316

Requisition #: MASP448STRGOL.05Q Date Shipped: 9-Sept-05

Lab Record #: VA05080697 Date Received: 20-Sept-05

Duplicates:	364062; 364082; 364102; 364122; 364142; 364162; 364182; 365202; 365222; 365242; 365262; 365282; 365302
Preparation Duplicate/ Check Assay:	364069; 364089; 364109; 364129; 364149; 364169; 364189; 365209; 365229; 365249; 365269; 365289; 365309
Standards:	364070 (6F); 364090 (2B); 364110 (4D); 364130 (5E); 364150 (6F); 364170 (2B); 364190 (6F); 365210 (3C); 365230 (2B); 365250 (7G); 365270 (3C); 365290 (6F); 365310 (4D)
Blanks:	364056; 364076; 364096; 364116; 364136; 364136; 364156; 364176; 364196; 365216; 365236; 365256; 365276; 365296; 365316

FROM	TO	LITHOLOGY
0.00	5.79	Casing; No Recovery
5.79	309.36	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96		-51.7	In casing	
121.91	325.7	-52.1	351.7	352.7
182.87	326.8	-52.3	352.8	353.8
243.83	329.2	-52.5	355.2	356.2
309.36	327.5	-52.7	353.5	354.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

At 445 ft and 465 ft, 10 foot blocks instead of 5 foot blocks were placed, therefore the hole was 10 feet shorter than originally recorded.

Reduced from HQ to NQ at 398 ft (121.30m) due to bad ground

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 1 of 12		
DRILL HOLE # : DG05-304C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0 - 5.79m	0.00	5.79	Casing - No Recovery						
10	5.79 - 27.43	5.79	27.43	GND: Grey GND is extremely weathered, broken up, and oxidized; Crumbly; @ 12.9 - 13.4m. GND competent and much less oxidized.	5					
10		27.43	60.96	GND: GND is highly oxidized; Is broken-up into angular blocks with local clay alteration (up to 50cm) from 33.36 - 33.86m (clay alt'd core is also carb-rich); Fractured blocks all limonite stained and commonly with carbonate on faces; Blocks can appear to have been previously sericite/chlorite altered; Slickenlines: @60.46m face at 15° with lines at 85° TCA; Siderite common in veinlets/fractures and as subhedral crystals disseminated within sericite altered core.	5	1		1	1	
10		60.96	83.82	GND: GND is much more competent, but still moderately broken up (8cm avg pieces); GND is only moderately oxidized - mostly restricted to fractures and veinlets and altered selvages; @60.96 - 62.28m core appears highly oxidized and sericitized (pale rusty colour) and also clay and carbonate altered; @ 64.89 - 65.53m core is intensely clay + carb altered; Appears brecciated (floating quartz-eyes); Slickenlines: @65.22m face at 5°, lines at 30°; @ 68.69m face at 15° with lines at 30°; @81.70m face at 45°, lines at 60°.	3	1				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation													
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.3	0.3	5														2.0				B364053	5.79	6.10	0.375			VA05080930	0.31
0																						B364054	6.10	7.62	1.855			VA05080930	1.52
0																						B364055	7.62	9.14	0.660			VA05080930	1.52
																						B364056	BLANK		<0.005			VA05080930	
0																						B364057	9.14	10.67	0.468			VA05080930	1.53
0																						B364058	10.67	12.19	0.892			VA05080930	1.52
0																						B364059	12.19	13.72	0.056			VA05080930	1.53
0																						B364060	13.72	15.24	4.110			VA05080930	1.52
0																						B364061	15.24	16.76	0.552			VA05080930	1.52
0																						B364062	15.24	16.76	0.125	DUP		VA05080930	1.52
0																						B364063	16.76	18.29	0.112			VA05080930	1.53
0																						B364064	18.29	19.81	1.140			VA05080930	1.52
2	1	20.0	25.0															4.0				B364065	19.81	21.34	10.000			VA05080930	1.53
																						B364066	21.34	22.86	0.026			VA05080930	1.52
																						B364067	22.86	24.38	0.009			VA05080930	1.52
																						B364068	24.38	25.91	0.024			VA05080930	1.53
																						B364069	24.38	25.91	0.023	PD/CA		VA05080930	1.53
																						B364070	STANDARD 3C		0.089	3C		VA05080930	
1	1	10.0	10.0																			B364071	25.91	27.43	2.660			VA05080930	1.52
1	1	3.0	3.0	20														2.0				B364072	27.43	28.96	1.350			VA05080930	1.53
1	1	1.0	1.0	60														2.0				B364073	28.96	30.48	0.069			VA05080930	1.52
0																						B364074	30.48	32.00	0.432			VA05080930	1.52
0																						B364075	32.00	33.53	0.224			VA05080930	1.53
																						B364076	BLANK		<0.005			VA05080930	
0																						B364077	33.53	35.05	0.487			VA05080930	1.52
0																						B364078	35.05	36.58	0.097			VA05080930	1.53
1	1	0.6	0.6	15		2.0		5	4									2.0				B364079	36.58	38.10	0.435			VA05080930	1.52
4	1	1.0	3.0	20		2.0	5	5	4									4.0				B364080	38.10	39.62	0.404			VA05080930	1.52
0																						B364081	39.62	41.15	0.155			VA05080930	1.53
0																						B364082	39.62	41.15	0.068	DUP		VA05080930	1.53
5	1	0.4	1.4	30														2.0				B364083	41.15	42.67	0.149			VA05080930	1.52
2	1	0.2	0.4	30														5.0				B364084	42.67	44.20	0.424			VA05080930	1.53
2	1	0.5	0.9	20														5.0				B364085	44.20	45.72	0.838			VA05080930	1.52
3	1	2.0	2.6	30														2.0				B364086	45.72	47.24	1.105			VA05080930	1.52
1	1	0.8	0.8	10														2.0				B364087	47.24	48.77	1.195			VA05080930	1.53
0																						B364088	48.77	50.29	0.082			VA05080930	1.52
0																						B364089	48.77	50.29	0.082	PD/CA		VA05080930	1.52
																						B364090	STANDARD 2B		3.130	2B		VA05080930	
0																						B364091	50.29	51.82	0.050			VA05080930	1.53
1	1	0.5	0.5	20														2.0				B364092	51.82	53.34	0.140			VA05080930	1.52
1	1	0.6	0.6	20														2.0				B364093	53.34	54.86	0.090			VA05080930	1.52
3	1	0.6	1.5	20														2.0				B364094	54.86	56.39	0.087			VA05080930	1.53
1	1	0.5	0.5	30														2.0				B364095	56.39	57.91	0.419			VA05080930	1.52
1	4	0.5	0.5	30														80.0											
																						B364096	BLANK		<0.005			VA05080930	
0																						B364097	57.91	59.44	0.205			VA05080930	1.53
0																						B364098	59.44	60.96	0.059			VA05080930	1.52
1	1	0.5	0.5	40														2.0				B364099	60.96	62.48	0.240			VA05080930	1.52
1	1	0.7	0.7	30														1.0				B364100	62.48	64.01	0.094			VA05080930	1.53
0																						B364101	64.01	64.89	0.029			VA05080930	0.88
0																						B364102	64.01	64.89	0.052	DUP		VA05080930	0.88

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 3 of 12		
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		83.82	89.92	GND: GND is highly fractured (full diameter of core is rare); Fractured faces are limonitic and react vigorously with HCl; Fracture faces with darker limonite staining only weakly react with HCl; Locally clay alteration is more intense at very shallow angles.	4			2		
10		89.92	92.96	GND: GND slightly less limonitic; GND moderately clay altered throughout with local intense clay alteration from 90.0 - 90.25m; Slight sericite alteration throughout (pale green color); Quartz veins vuggy from previous sulphides; Slickenlines: @92.36m face at 30°, lines at 45°.	2	2		3		
10		92.96	96.01	GND: Fairly competent and unaltered GND; Fracture faces with limonite and commonly with carb/calcite; Limonite selvages common with fractures.	1					
10		96.01	101.04	GND: GND is moderately limonitic; Core is highly broken, with rare full diameter core; Quartz veins are vuggy from previous sulphides.	1					
10		101.04	115.82	GND: Unaltered GND, very competent, grey in color; Limonite staining still present on fracture surfaces; Only very minor limonite selvages along fractures; Quartz veins are predominantly grey with distinct edges.						
10		115.82	127.75	GND: Grey GND which has been moderately oxidized; Core is moderately broken up (10cm avg); Fracture faces are limonitic, commonly with carbonate and calcite; Locally core is highly broken up (117.35 - 118.45m); Core reduces to NQ at 121.56m	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

PAGE 4 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
0																						B364103	64.89	65.53	0.030			VA05080930	0.64
1	1	0.3	0.3	60														1.0				B364104	65.53	67.06	0.312			VA05080930	1.53
3	1	0.6	1.4	45	30													2.0				B364105	67.06	68.58	0.071			VA05080930	1.52
3	1	0.5	1.0	30														2.0				B364106	68.58	70.10	0.181			VA05080930	1.52
0																						B364107	70.10	71.63	0.048			VA05080930	1.53
3	1	1.0	1.4	40														2.0				B364108	71.63	73.15	0.208			VA05080930	1.52
3	1	1.0	1.4	40														2.0				B364109	71.63	73.15	0.233	PD/CA		VA05080930	1.52
																						B364110	STANDARD 4D		0.439	4D		VA05080930	
4	1	1.0	2.1	40	30						1.0											B364111	73.15	74.68	0.228		Po in one vein only	VA05080930	1.53
1	1	0.3	40.0															4.0				B364112	74.68	76.20	0.056			VA05080930	1.52
1	3	2.0	70.0															60.0											
1	1	1.5	1.5	30														2.0				B364113	76.20	77.72	0.185			VA05080930	1.52
5	1	2.0	5.0	40														2.0				B364114	77.72	79.25	0.084			VA05080930	1.53
3	1	1.2	16.0	30		0.5	q	5										2.0				B364115	79.25	80.77	0.141			VA05080930	1.52
																						B364116	BLANK		<0.005			VA05080930	
1	1	1.0	1.0	15						4.0	2.0							2.0				B364117	80.77	82.30	0.012			VA05080930	1.53
3	1	0.5	1.0	40																		B364118	82.30	83.82	<0.005			VA05080930	1.52
1	1	0.5	0.5	45														2.0				B364119	83.82	85.34	0.287			VA05080930	1.52
3	1	0.5	1.0	45														3.0				B364120	85.34	86.87	0.078			VA05080930	1.53
2	1	0.4	0.8	45														3.0				B364121	86.87	88.39	0.076			VA05080930	1.52
2	1	0.4	0.8	45														3.0				B364122	86.87	88.39	0.071	DUP		VA05080930	1.52
1	6	0.5	0.5	40														60.0				B364123	88.39	89.92	0.069			VA05080930	1.53
2	1	0.5	0.9	45														2.0				B364124	89.92	91.44	0.069			VA05080930	1.52
1	1	0.5	0.5	30														5.0				B364125	91.44	92.96	0.025			VA05080930	1.52
2	1	0.7	1.1	45						0.1	2.0		3.0					2.0				B364126	92.96	94.49	0.240			VA05080930	1.53
1	5	0.5	0.5	45									5.0																
1	1	1.5	1.5	40						1.0			10.0									B364127	94.49	96.01	0.148			VA05080930	1.52
1	1	0.5	0.5	45														2.0				B364128	96.01	97.54	0.035			VA05080930	1.53
1	1	0.5	0.5	45														2.0				B364129	96.01	97.54	0.042	PD/CA		VA05080930	1.53
																						B364130	STANDARD 5E		1.440	5E		VA05080930	
1	1	0.5	0.5	40														2.0				B364131	97.54	99.06	0.082			VA05080930	1.52
2	1	0.5	1.0	45														2.0				B364132	99.06	100.58	0.185			VA05080930	1.52
0																						B364133	100.58	101.04	0.231			VA05080930	0.46
4	1	1.0	2.5	40		0.5	q	3			5.0											B364134	101.04	102.26	0.157			VA05080930	1.22
5	1	1.0	3.5	45	20	1.5	q	2			4.0											B364135	102.26	103.63	0.120			VA05080930	1.37
1	4	0.5	0.5	45														1.0											
																						B364136	BLANK		<0.005			VA05080930	
9	1	1.4	5.5	45		1.0	q	3			3.0											B364137	103.63	105.16	0.721			VA05080930	1.53
7	1	0.5	3.0	45							2.0											B364138	105.16	106.68	0.235			VA05080930	1.52
10	1	1.2	5.6	40		1.0	q	2			2.0											B364139	106.68	108.20	0.120			VA05080930	1.52
7	1	1.0	5.0	40		1.0	q/chl	4			4.0											B364140	108.20	109.73	0.218			VA05080930	1.53
2	1	0.6	1.2	40							2.0											B364141	109.73	111.25	0.048			VA05080930	1.52
2	1	0.6	1.2	40							2.0											B364142	109.73	111.25	0.086	DUP		VA05080930	1.52
10	1	1.0	6.2	45																		B364143	111.25	112.78	0.197			VA05080930	1.53
4	1	1.0	2.3	45	30						7.0	0.1										B364144	112.78	114.30	0.165			VA05080930	1.52
2	1	1.2	1.5								5.0		2.0									B364145	114.30	115.82	0.235			VA05080930	1.52
1	6	0.2	0.2	30		2.0	q/s	4			50.0		10.0																
4	1	0.8	2.0	40		0.3	q/s	5		0.1	5.0		1.0					1.0				B364146	115.82	117.35	0.243			VA05080930	1.53
4	1	1.0	2.5	40														2.0				B364147	117.35	118.87	0.091			VA05080930	1.52
8	1	1.0	4.5	45							2.0							2.0				B364148	118.87	120.40	0.253			VA05080930	1.53
8	1	1.0	4.5	45							2.0							2.0				B364149	118.87	120.40	0.865	PD/CA		VA05080930	1.53
																						B364150	STANDARD 6F		2.760	6F		VA05080930	
2	1	0.7	1.0	45							2.0											B364151	120.40	121.92	0.109			VA05080930	1.52

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 5 of 12		
DRILL HOLE # : DG05-304C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		127.75	150.05	GND: GND appears unaltered and very competent; Fractures are limonitic with calcite/carbonate; Starting to see chlorite along fractures as well; @148.35 - 149.9m core is highly fractured (up to 4cm full diameter core), limonitic throughout with moderate clay alteration. Slickenlines: @150.25m face at 50° with lines at 150° TCA.						
10		150.05	176.77	GND: Very competent GND; GND is unaltered; no limonite visible; minor carbonate/calcite on fractures throughout; Carb/calcite fractures commonly have pale-green color due to chlorite +/- sericite; Rare fine grained biotite blebs (up to 4x4cm) observed in GND (no mineralization associated); Disseminated and locally smeared pyrite common on fracture faces; @ 172.23 - 172 m core is highly oxidized, crumbly and clay altered in contact with (30°) 12cm silicified and chloritized GND. Slickenlines: @ 159.5m face at 45° with lines at 45°; @ 164.35m face at 35° with lines at 35°; @ 175.32m face at 80° with lines at 80°; @ 175.46m face at 30° with lines at 70°; @ 179.3m face at 20° with lines at 20° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

PAGE 6 of 12

Selvage Alteration: ehl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ce = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
5	1	0.8	1.6	40							2.0											B364152	121.92	123.44	0.198			VA05080930	1.52
5	1	0.5	1.6	40							2.0							1.0				B364153	123.44	124.96	0.067			VA05080930	1.52
1	3	0.5	0.5	40							2.0											B364154	124.96	126.49	0.025			VA05080930	1.53
1	1	0.4	0.4	40														2.0											
3	1	0.5	1.0	40	60	1.0	q	5			2.0		1.0					1.0				B364155	126.49	127.75	0.066			VA05080930	1.26
																						B364156	BLANK		<0.005			VA05080930	
5	1	1.0	2.2	40							2.0		1.0					1.0				B364157	127.75	129.54	0.046			VA05080930	1.79
7	1	1.0	4.0	40							3.0		0.1				0.1					B364158	129.54	131.07	0.075		Moly	VA05080930	1.53
3	1	0.6	1.5	40							2.0							1.0				B364159	131.07	132.59	0.736			VA05080930	1.52
7	1	0.6	4.2	40							4.0	0.1	0.1				0.1					B364160	132.59	134.11	0.281		Moly	VA05080930	1.52
3	1	0.3	0.7	40							2.0											B364161	134.11	135.64	0.041			VA05080930	1.53
3	1	0.3	0.7	40							2.0											B364162	134.11	135.64	0.033	DUP		VA05080930	1.53
2	1	1.0	1.2	40		0.5	q	5			2.0							1.0				B364163	135.64	137.16	0.039			VA05080930	1.52
3	1	1.0	1.6	40							2.0				0.1							B364164	137.16	138.68	0.171			VA05080930	1.52
3	1	1.0	1.9	40	60						1.0	0.1										B364165	138.68	140.20	0.039			VA05080930	1.52
1	5	1.0	1.0	40		0.3	q	5			2.0	0.1	0.1																
2	1	0.5	0.9	40	60						4.0	0.1										B364166	140.20	141.73	0.078			VA05080930	1.53
1	5	1.0	1.0	40							1.0																		
10	1	1.0	4.5	45	60	0.5	q	5			2.0	0.1	1.0									B364167	141.73	143.25	0.091			VA05080930	1.52
2	1	0.5	0.8	40							2.0		0.1									B364168	143.25	144.78	0.081			VA05080930	1.53
2	1	0.5	0.8	40							2.0		0.1									B364169	143.25	144.78	0.038	PD/CA		VA05080930	1.53
																						B364170	STANDARD 2B		2.910	2B		VA05080930	
0																						B364171	144.78	145.30	0.018			VA05080930	0.52
1	1	0.5	0.5	40														2.0				B364172	145.30	146.85	0.061			VA05080930	1.55
0																						B364173	146.85	147.83	0.066			VA05080930	0.98
8	1	0.8	4.0	40	60						2.0											B364174	147.83	148.93	0.077			VA05080930	1.10
3	1	1.0	2.0	40							1.0											B364175	148.93	150.05	0.229			VA05080930	1.12
																						B364176	BLANK		<0.005			VA05080930	
1	1	1.0	1.0	40							2.0											B364177	150.05	150.88	0.045			VA05080930	0.83
1	4	0.4	0.4	##																									
1	5	0.5	0.5	40							1.0																		
5	1	0.4	1.5	40							2.0	0.1					0.1					B364178	150.88	152.40	0.041		Moly	VA05080930	1.52
1	3	0.5	0.5	60							2.0																		
4	1	1.0	3.0	40							5.0	0.1	1.0				0.1					B364179	152.40	153.93	1.465			VA05080930	1.53
1	1	1.0	1.0	50									2.0									B364180	153.93	155.45	0.483			VA05080930	1.52
1	1	1.5	1.5	80							0.1	0.1										B364181	155.45	156.97	0.046			VA05080697	1.52
1	1	1.5	1.5	80							0.1	0.1										B364182	155.45	156.97	0.029	DUP		VA05080697	1.52
6	1	1.2	3.0	40		0.2	q	5			2.0		2.0									B364183	156.97	158.50	0.106			VA05080697	1.53
2	1	0.5	1.0	40	60						1.0											B364184	158.50	160.02	0.032			VA05080697	1.52
1	5	0.5	0.5	50						10.0	4.0		1.0																
3	1	0.8	1.4	40							2.0		1.0									B364185	160.02	161.55	0.105			VA05080697	1.53
6	1	1.2	3.0	40							2.0		1.0									B364186	161.55	163.07	0.135			VA05080697	1.52
3	1	0.5	1.2	30	40	0.3	q	5			1.0											B364187	163.07	164.60	0.196			VA05080697	1.53
6	1	1.8		45	35	0.2	q	5			3.0	0.1	1.0									B364188	164.60	166.12	0.152			VA05080697	1.52
6	1	1.8		45	35	0.2	q	5			3.0	0.1	1.0									B364189	164.60	166.12	0.148	PD/CA		VA05080697	1.52
																						B364190	STANDARD 6F		2.820	6F		VA05080697	
3	1	0.5	1.2	40							2.0		0.1									B364191	166.12	167.65	0.100			VA05080697	1.53
1	6	0.5	0.5	40							30.0	0.1	1.0																
1	1	0.8	0.8	35																		B364192	167.65	169.16	0.060			VA05080697	1.51
1	1	0.4	0.4	45														1.0				B364193	169.16	169.83	0.085			VA05080697	0.67
3	1	0.6	1.0	35	65						1.0	0.1										B364194	169.83	170.65	0.027			VA05080697	0.82
3	1	15.0	2.0	60	45						1.0											B364195	170.65	172.21	0.029			VA05080697	1.56

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 7 of 12		
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		176.77	179.80	GND: Grey GND, unaltered; Similar to previous interval (153.1 - 179.84m) but fractures are limonitic again +/- carb/calcite; Core moderately broken up (12cm avg).						
10		179.80	193.85	GND: GND is very broken up (3x3x11.5cm, avg); with unaltered GND (10cm, avg.); Broken core limonitic with carbonate on faces; Blocks of broken core are softer - clay alteration; @193.85m - 194.27m = Core is intensely clay altered and carbonate altered with slickenlines at contact (up hole), face is at 15° with lines at 30° TCA.	2			2		
10		193.85	197.38	GND: GND is very soft (clay/argillic alteration) with moderate carbonate alteration throughout; Core has a slight greenish hue; From 193.85 - 194.25m core is clay and appears brecciated (floating quartz clasts and soft GND clasts); @ 196.35 - 197.38m core is limonitic with evidence of massive pyrite vein (0.5cm). Slickenlines: @194.47m face is at 5° with lines at 40°, @195.00m face is at 65° with lines at 80° TCA.		1		5	3	
10		197.38	225.13	GND: GND similar to interval 179.8 - 193.85m but majority of broken blocks are not clay altered; @ 201.55m VG is observed with aspy within chloritic bleb between 2 adjacent grey quartz veins (0.4cm each) at 45° TCA - quartz veins have minor carb and chlorite throughout; One 1.4cm q/chl altered selvage observed along veins; Veins contain ~5% pyrrhotite and 2% aspy; Local sericite alteration from 211.66 - 212.48m with minor carbonate alteration; @ 214.98 - 215.07m intensive clay and carbonate alteration with sharp down hole contact at 40° with slickenlines at 70°; Slickenlines: @ 215.09m face at 5° and lines at 5°; @ 224.43m, face at 5° with lines at 40°.	2					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

PAGE 8 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
																						B364196	BLANK		<0.005			VA05080697	
5	1	1.0	3.5	60	30						2.0						0.1					B364197	172.21	173.74	0.090		Moly	VA05080697	1.53
3	1	1.0	1.6	35	85						2.0						0.1					B364198	173.74	175.26	0.025		Moly	VA05080697	1.52
1	5	2.0	2.0	55						1.0																			
1	5	0.5	0.5	40		15.0	q/chl	5			1.0	0.1										B364199	175.26	176.77	0.028			VA05080697	1.51
2	1	1.0	1.5	45							1.0																		
4	1	1.0	2.2	40	50	2.0	q/chl	5			1.0											B364200	176.77	178.31	0.051			VA05080697	1.54
1	1	0.7	0.7	45																		**B365201**	178.31	179.80	0.049		**New Sample Book**	VA05080697	1.49
1	5	0.4	0.4	40		1.5	q/chl	4																					
1	3	0.3	0.3	40		0.5	q/chl	5			2.0	0.1																	
1	1	0.7	0.7	45																		B365202	178.31	179.80	0.045	DUP		VA05080697	1.49
1	5	0.4	0.4	40		1.5	q/chl	4																					
1	3	0.3	0.3	40		0.5	q/chl	5			2.0	0.1																	
0																						B365203	179.80	181.36	0.038			VA05080697	1.56
0																						B365204	181.36	182.88	0.598			VA05080697	1.52
1	1	0.3	0.3	40		0.3	q	s			2.0	0.1										B365205	182.88	184.40	0.034			VA05080697	1.52
3	1	0.4	1.2	40		0.3	q	4			2.0	0.1										B365206	184.40	185.92	0.095			VA05080697	1.52
1	1	0.2	0.2	45																		B365207	185.92	187.45	0.036			VA05080697	1.53
0																						B365208	187.45	188.98	0.026			VA05080697	1.53
0																						B365209	187.45	188.98	0.025	PD/CA		VA05080697	1.53
																						B365210	STANDARD 3C		0.093	3C		VA05080697	
1	1	0.4	0.4	35																		B365211	188.98	190.50	0.039			VA05080697	1.52
0																						B365212	190.50	192.15	0.013			VA05080697	1.65
0																						B365213	192.15	193.85	0.037			VA05080697	1.70
1	6	0.5	0.5	65						80.0												B365214	193.85	195.38	0.104			VA05080697	1.53
0																						B365215	195.38	197.38	0.176			VA05080697	2.00
																						B365216	BLANK		<0.005			VA05080697	
5	1	1.0	2.0	65	50	0.6	q/chl	5			3.0											B365217	197.38	198.90	0.420			VA05080697	1.52
1	5	0.5	0.5	50		0.5	q/chl	4			3.0																		
3	1	0.5	1.0	60		1.0	s/chl	4			1.0							5.0				B365218	198.90	199.64	0.128			VA05080697	0.74
2	5	0.8	1.2	60		0.2	q/chl	5			2.0		0.1																
9	1	1.0	6.0	60	80	1.0	q/chl	5			1.0							2.0				B365219	199.64	201.16	0.933			VA05080697	1.52
7	1	1.3	5.0	45		1.4	q/chl	4			2.0		1.0			0.1	0.1					B365220	201.16	202.69	0.084		Moly	VA05080697	1.53
2	1	0.5	1.8	45		1.0	q/chl	3			1.0											B365221	202.69	204.21	0.182			VA05080697	1.52
2	1	0.5	1.8	45		1.0	q/chl	3			1.0											B365222	202.69	204.21	0.161	DUP		VA05080697	1.52
3	1	1.5	4.5	60						2.0								2.0				B365223	204.21	205.74	0.069			VA05080697	1.53
1	3	1.2	30.0															5.0											
2	1	1.5	2.0	60														1.0				B365224	205.74	207.26	0.429			VA05080697	1.52
3	1	0.5	1.1	45	60	0.5	q/chl	3														B365225	207.26	208.79	0.018			VA05080697	1.53
1	1	0.5	0.5	30																		B365226	208.79	210.32	0.297			VA05080697	1.53
2	1	0.5	1.0	30	45						5.0											B365227	210.32	211.66	0.264			VA05080697	1.34
1	6	0.5	0.5	45									25.0																
1	1	0.3	0.3	45							1.0											B365228	211.66	212.48	0.040			VA05080697	0.82
1	1	0.3	0.3	45							1.0											B365229	211.66	212.48	0.045	PD/CA		VA05080697	0.82
																						B365230	STANDARD 2B		1.705	2B		VA05080697	
4	1	1.0	2.5	45		1.5	s	4			2.0											B365231	212.48	213.95	1.370			VA05080697	1.47
1	3	0.3	0.3	45							1.0																		
1	1	0.8	0.8	45						1.0												B365232	213.95	214.88	0.086			VA05080697	0.93
1	5	1.0	1.0	45																									
4	1	2.5	4.8	60	45						1.0											B365233	214.88	216.40	0.122			VA05080697	1.52

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 9 of 12		
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; QVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		225.13	225.74	GND: Core is extremely clay altered and sericite altered; Random clasts of calcite (0.5cm avg) throughout; Slickenlines at 225.37m with face at 45° and lines at 45° TCA; Sharp contact at both ends @ 35° TCA; Dark grey clay observed on fracture faces.		4		5	3	
10		225.74	228.00	GND: GND is highly fractured; Pieces of core average 2x2x2.5cm in size; Fracture faces are limonitic with white calcite on the surfaces; Rare pieces are very clay altered and limonitic throughout.	3					
10		228.00	246.23	GND: Grey GND is moderately broken up (5cm avg); Fracture faces have white calcite with sericite +/- chlorite alteration; GND has minor sericite alteration throughout; Clay alteration occurs locally from 234.7 - 234.85m with heavily fractured quartz veins. Slickenlines: @ 237.9m face at 40° and lines at 40°; @ 238.87m face at 30° with lines at 75°; @ 242.2m face at 5° with lines at 20°; @ 244.9m face at 30° with lines at 50°; @ 244.9m face at 5° with lines at 50°; @ 245.36m face at 20° with lines at 45° TCA.		2				
10		246.23	249.67	GND: GND is very sericite altered; Only quartz remains unaltered; Core is also moderately carbonate altered throughout; Locally core is extremely clay altered: from 246.55 - 246.75m (broken up qv with v f gr diss py), 248.38 - 248.54m, 249.56 - 249.67m; From 247.48 - 247.63m = 2 irregular sulphide veins (30° and 60° contact) ~3cm with black oxidized pyrite? and disseminated f gr euhedral pyrite; @ 247.19m = ~1cm q v is broken - irregular/displaced wi v f gr diss py; Between qv at 247.19m and sulphide veins at 247.48m is very sericitic core wi v f gr diss py blebs throughout (~12%); Slickenlines: @248.54m face at 30° with lines at 60° TCA.		4			3	
10		249.67	291.57	GND: GND similar as described from 228 - 246.23m but with intervals of intense ser + carb alteration; From 271.67 - 271.92m core is very silicified and slightly sericite altered; Rare pyrite and pyrrho vnlts found throughout ser alt'd core; Ser alt'd intervals @ 253.42 - 254.28m, 258.67 - 260.60m, 263.65 - 264.47m and 273.2 - 273.88m; Slickenlines: @ 253.2m 50°/80°, @ 255.3m 30°/75°, @257.4m 5°/45°, @262.12m 30°/60°, @266.0m 40°/40°, @278.15m 5°/70°, @285.44m 40°/45°, @290.5m 20°/50° TCA; Sericite alt'n from 286.07 - 286.38m.		2			2	

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS											% of VEIN & DISSEMINATED MATERIAL													Interval						
						Selvages				Sulphides								Oxidation				Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other								
0																						B365234	216.40	217.93	0.061			VA05080697	1.53
3	1	0.5	1.2	60							0.1											B365235	217.93	219.45	0.056			VA05080697	1.52
																						B365236	BLANK		<0.005			VA05080697	
2	1	0.6	1.2	40							1.0											B365237	219.45	220.98	0.100			VA05080697	1.53
2	1	0.5	0.5	45							0.1											B365238	220.98	222.50	0.154			VA05080697	1.52
2	1	0.5	0.9	30	40						1.0											B365239	222.50	224.03	0.964			VA05080697	1.53
1	1	0.8	0.8	60									0.1									B365240	224.03	225.13	1.620			VA05080697	1.10
0																						B365241	225.13	225.74	0.110			VA05080697	0.61
0																						B365242	225.13	225.74	0.037	DUP		VA05080697	0.61
0																						B365243	225.74	227.08	0.114			VA05080697	1.34
0																						B365244	227.08	228.00	0.187			VA05080697	0.92
0																						B365245	228.00	228.96	0.033			VA05080697	0.96
2	1	0.6	1.0	30	45						1.0											B365246	228.96	230.12	0.212			VA05080697	1.16
1	6	0.4	0.4	45		0.3	q/s	5			30.0																			
2	1	0.5	1.0	30	45						1.0											B365247	230.12	231.65	0.058			VA05080697	1.53
3	1	2.0	4.2	45		3.0	s/q	4		1.0												B365248	231.65	233.17	1.055			VA05080697	1.52
3	1	2.0	4.2	45		3.0	s/q	4		1.0												B365249	231.65	233.17	0.643	PD/CA		VA05080697	1.52
																						B365250	STANDARD 7G		4.710	7G		VA05080697	
1	1	0.3	0.3	30																		B365251	233.17	234.70	0.077			VA05080697	1.53
3	1	0.5	1.3	45	35	0.3	q	5			1.0											B365252	234.70	236.22	0.141			VA05080697	1.52
1	1	1.0	1.0	45		0.2	q	5														B365253	236.22	237.75	0.093			VA05080697	1.53
1	1	0.7	0.7	45							1.0											B365254	237.75	239.27	0.119			VA05080697	1.52
3	1	0.5	1.3	40	50	0.5	q	5			4.0	0.1										B365255	239.27	240.80	0.371			VA05080697	1.53
																						B365256	BLANK		<0.005			VA05080697	
1	5	0.5	0.5	50							2.0											B365257	240.80	242.32	0.064			VA05080697	1.52
1	1	0.5	0.5	60																									
1	1	0.5	0.5	60																		B365258	242.32	243.85	0.134			VA05080697	1.53
1	1	0.8	0.8	85																		B365259	243.85	245.36	0.033			VA05080697	1.51
1	1	1.0	1.0	85		0.4	s/q	5														B365260	245.36	246.23	0.032			VA05080697	0.87
0																						B365261	246.23	247.15	0.216			VA05080697	0.92
0																						B365262	246.23	247.15	0.549	DUP		VA05080697	0.92
3	6	3.0	7.0	45	30					50.0												B365263	247.15	247.63	6.330		Sulphides	VA05080697	0.48
2	1	0.5	0.7	45																		B365264	247.63	248.41	1.735			VA05080697	0.78
0																						B365265	248.41	249.67	0.091			VA05080697	1.26
0																						B365266	249.67	251.46	0.391			VA05080697	1.79
3	1	1.0	2.0	60							2.0											B365267	251.46	252.98	0.853			VA05080697	1.52
3	1	1.0	1.2	60							1.0											B365268	252.98	254.51	0.205			VA05080697	1.53
3	1	1.0	1.2	60							1.0											B365269	252.98	254.51	0.287	PD/CA		VA05080697	1.53
																						B365270	STANDARD 3C		0.093	3C		VA05080697	
2	1	2.0	3.0	80							2.0											B365271	254.51	256.03	0.630			VA05080697	1.52
1	1	2.0	2.0	85							0.1											B365272	256.03	257.56	0.236			VA05080697	1.53
2	1	0.8	1.6	45							2.0											B365273	257.56	259.09	1.265			VA05080697	1.53
2	1	0.4	0.7	60	85					1.0	1.0											B365274	259.09	260.60	0.778			VA05080697	1.51
2	1	0.5	1.0	80																		B365275	260.60	262.12	0.166			VA05080697	1.52
																						B365276	BLANK		<0.005			VA05080697	

DRILL LOG LEGEND P1	DATE: Aug 28 - Sept 1, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05-304C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		291.57	300.23	GND has a greyish-green colour; Sericite alteration is prominent throughout except for various short (10cm) intervals of unaltered GND. K-spar is observed along quartz veins in selvages and as veinlets and euh-subhedral grains diss throughout ser alt'd core; Fractured faces commonly have black-dark green color (chl and biot); From 291.57 - 291.77m core is extremely clay and carb alt'd with brecciated quartz clasts/eyes; Interval 295.65 - 297.18m (B365305) wi qtz vn showing dextral displacement ~2cm at various angles; Slickenline: @192.07m face at 40° with lines at 50°; @294.0m 5°/5°; @295.75m 0°/45°.		4				3
		300.23	309.37	GND: Moderately fractured unaltered grey GND (8cm avg); Fracture faces contain white calcite with slight ser-+/- chl alteration; Local moderate clay alteration from 304.8 - 305.25m; 309.27 - 309.57m = fine grained "mafic" GND with weak ser alteration; Slickenlines: @303.7m face at 40° with lines at 45°; @ 205.35m = 5°/65°; @ 305.4m = 30°/50°; @ 306.7m = 5°/90°; @ 309.27m = 5°/85°.						
				E.O.H.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 28 - September 1, 2005

LOGGED BY: K. Piepgrass

PAGE 12 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																					
						Selvages				Sulphides									Oxidation					Interval							
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
6	1	2.4	6.0	65	30	7.0	s/cb	5			4.0											B365277	262.12	263.65	**0.595**			VA05080697	1.53
3	1	1.2	2.2	65							2.0											B365278	263.65	265.18	**0.050**			VA05080697	1.53
1	3	0.8	0.8	60																									
1	1	0.5	0.5	65																		B365279	265.18	266.70	**0.136**			VA05080697	1.52
1	1	1.0	1.0	75							2.0											B365280	266.70	268.22	**0.088**			VA05080697	1.52
1	5	0.8	0.8	60																		B365281	268.22	269.75	**0.064**			VA05080697	1.53
1	5	0.8	0.8	60																		B365282	268.22	269.75	**0.054**	DUP		VA05080697	1.53
6	1	1.0	4.5	80	60						2.0											B365283	269.75	271.27	**0.420**			VA05080697	1.52
1	1	0.5	0.5	45							1.0											B365284	271.27	272.80	**0.613**			VA05080697	1.53
3	1	1.6	2.2	60							1.0											B365285	272.80	274.33	**0.361**			VA05080697	1.53
4	1	1.0	3.8	70	45	3.0	q/s	5			0.1											B365286	274.33	275.84	**0.081**			VA05080697	1.51
1	4	0.6	0.6	45																									
6	1	0.7	2.5	60							1.0											B365287	275.84	277.16	**0.477**			VA05080697	1.32
2	5	0.4	0.7	60		0.5	q	5			2.0											B365288	277.16	278.89	**1.775**			VA05080697	1.73
2	3	1.0	1.5	60		0.4	q	5			2.0																		
2	5	0.4	0.7	60		0.5	q	5			2.0											B365289	277.16	278.89	**1.985**	PD/CA		VA05080697	1.73
2	3	1.0	1.5	60		0.4	q	5			2.0																		
																						B365290	STANDARD 6F		**2.870**	6F		VA05080697	
8	1	1.0	4.5	60	45						1.0		0.1									B365291	278.89	280.42	**0.305**			VA05080697	1.53
1	1	0.5	0.5	60							1.0											B365292	280.42	281.94	**0.940**			VA05080697	1.52
1	5	1.0	1.0	60		2.0	q/chl	5			1.0																		
7	1	0.5	2.2			0.4	q/chl	5			2.0											B365293	281.94	283.46	**0.396**			VA05080697	1.52
1	3	0.5	0.5	0		1.0	q/s	5			1.0																		
5	1	0.8	2.7	60	0	0.3	q	5			1.0											B365294	283.46	284.99	**0.103**			VA05080697	1.53
3	1	0.7	1.4	45	15	0.5	q/s	4			1.0											B365295	284.99	286.52	**0.199**			VA05080697	1.53
																						B365296	BLANK		**<0.005**			VA05080697	
1	1	0.6	0.6	40																		B365297	286.52	288.04	**0.199**			VA05080697	1.52
1	3	0.4	0.4	40						2.0																			
1	1	0.6	0.6	30																		B365298	288.04	289.56	**0.055**			VA05080697	1.52
1	6	0.3	0.3	45							30.0																		
1	1	0.2	0.2	40							2.0											B365299	289.56	291.08	**0.583**			VA05080697	1.52
2	1	0.5	0.7	30							2.0											B365300	291.08	291.57	**4.480**			VA05080697	0.49
1	1	0.5	0.5	45						2.0												B365301	291.57	292.84	**2.780**			VA05080697	1.27
1	1	0.5	0.5	45						2.0												B365302	291.57	292.84	**7.530**	DUP		VA05080697	1.27
1	1	0.5	0.5	25						5.0												B365303	292.84	294.13	**0.335**			VA05080697	1.29
1	2	1.2	1.2	65		5.0	s/k	5														B365304	294.13	295.65	**0.360**			VA05080697	1.52
1	1	0.8	0.8	85						10.0																			
4	1	1.0	2.5	45	60						1.0											B365305	295.65	297.18	**0.284**			VA05080697	1.53
1	2	0.6	0.6	45																									
3	1	1.0	2.2	45	10	1.0	s/k	5		5.0	1.0											B365306	297.18	298.70	**0.059**		Py only in 1 vn	VA05080697	1.52
4	1	1.0	3.0	60						2.0												B365307	298.70	300.23	**0.677**			VA05080697	1.53
1	6	4.0	4.0	65						40.0																			
1	1	0.2	0.2	60							1.0											B365308	300.23	301.75	**0.126**			VA05080697	1.52
1	1	0.2	0.2	60							1.0											B365309	300.23	301.75	**0.076**	PD/CA		VA05080697	1.52
																						B365310	STANDARD 4D		**0.466**	4D		VA05080697	
2	1	0.3	0.6	45							1.0											B365311	301.75	303.28	**0.055**			VA05080697	1.53
4	1	1.5	2.8	45	10					1.0	2.0		0.1									B365312	303.28	304.80	**0.457**			VA05080697	1.52
0																						B365313	304.80	306.32	**0.156**			VA05080697	1.52
1	1	0.4	0.4	20							1.0											B365314	306.32	307.85	**0.254**			VA05080697	1.53
1	1	1.0	1.0	45																		B365315	307.85	309.37	**0.484**			VA05080697	1.52
																						B365316	BLANK		**<0.005**			VA05080697	

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-305C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1111m

BEARING: 180 | DIP: -55

DATES DRILLING: Aug 10-15, 2005

DATES LOGGING: Aug 27 - Sept 1, 2005

LOGGED BY: Molodie Stone

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459907 NORTHING: 7099589

COORD SYSTEM: NAD 83: EASTING: 459789 NORTHING: 7099774

NAD 27 (CORRECTED for historic grid): EASTING: 459877 NORTHING: 7099599

SECTION LINE(historic grid): 459875 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 1.52m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	1.52	Casing
1.52	99.27	MSED (HFLS)
99.27	102.11	GND
102.11	106.40	MSED (HFLS)
106.40	259.08	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B364700-B364740

Requisition #: MASP448STRGOL.05Q Date Shipped: 9-Sept-05

Lab Record #: VA05080696 Date Received: 20-Sept-05

Sample Sequence: B364741 - B364873

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Sept-05

Lab Record #: VA05082980 Date Received: 27-Sept-05

Duplicates:	364702; 364722; 364742; 364762; 364782; 364802; 364822; 364842; 364862
Preparation Duplicate/ Check Assay:	364709; 364729; 364749; 364769; 364789; 364809; 364829; 364849; 364869
Standards:	364710 (4D); 364730 (4D); 364750 (7G); 364770 (6F); 364790 (2B); 364810 (4D); 364830 (3C); 364850 (5E); 364870 (2B)
Blanks:	364716; 364736; 364756; 364776; 364796; 364816; 364836; 364856

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	151.3	-53.8	177.3	178.3
121.91	151.4	-55.3	177.4	178.4
182.87	150.3	-56.5	176.3	177.3
259.07	151.1	-57.0	177.1	178.1

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

Tight hole at the top; Reamed casing down to 74 ft

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 1 of 10	
DRILL HOLE # : DG05-305C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10	0-1.52	0.00	1.52	Casing						
81	1.52 - 9.14	1.52	9.14	HFLS: Deep purple and aphanitic. Banded with light brown-grey layers on a 1-2cm scale throughout section; minor rusty orange-brown on irregular fracture faces, also with late carbonate, sometimes incorporated as layers within this banded rock; Pale grey layers are silicified hard (cordierite), deep purple layers are scratchable with scriber; Foliations: @2.0m = 80-90°, @4.0m = 40°; @ 6.0m = 35°; @ 8.0m = 30°.	2	0	0	0	1	
80	9.14-23.78	9.14	23.78	MSED: Zone of brecciated MSED; No complete diameter core until 22.40 - 22.86m where oxidized MSED has a general foliation of 40°; Recovery btwn 5 and 42% except btwn 10.67-12.19m and from 22.86 - 23.78m where it improves, but is still crumbly, with oxidized, convoluted metabeds; Argillaceous alteration throughout section, related to sericitic replacement along metabeds; One sample taken from this section where one qtz vein cuts competent, complete core and pebbles are rich in pure quartz. Only trace oxidized pyrite present.	4	3	0	3	2	
81	23.78	23.78	28.56	Competent HFLS; Metabeds folded in places - open, rounded and box folds; Pale grey layers (mentioned from 1.52-9.14m) not present here; Quartz and quart/carb veins cut across foliation but contain no sulphides or gold.	1	1		1	1	
80	28.56-38.10	28.56	32.00	MSED: Sheared/brecciated MSED; Sample taken from 30.48-32.0m because oxidation and shear have made this section of variable composition ("mixed bag" of MSED's).	4	2		4	3	
80		32.00	38.10	MSED: Strong banding; Quartz veins incorporation into foliation.						
81	38.10-99.27	38.10	44.20	MSED: HFLS with 'globular' veins of pure quartz, incorporated into MSED foliation. Few crosscut (noted); Very deep purple to purplish grey here.	1	0	0	0	1	
81		44.20	47.92	MSED: Oxidized (light brown) zone, stemming into foliation from quartz veins; These veins have calcite int the centre very few sulphides; Still HFLS; From 44.15 - 46.8m is all oxidized, weakened MSED.	3	1		1	2	
81		47.92	57.41	MSED: HFLS with pure quartz incoroporated into foliation; This quartz may have once been veins; Few 'new' veins (crosscutting) have trace oxidized pyrite and occassionally aspy.					1	
81		57.41	60.48	MSED: Competent HFLS with incorporated quartz into foliation and few wide crosscutting quartz veins with noticeable selvages; Micaceous replacement of semthing (sulphides?) preset within some veins.		1	1		1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

PAGE 2 of 10

Selvage Alteration: phl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar,, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																							1.52	3.05					1.53
0																							3.05	4.57					1.52
0																							4.57	6.10					1.53
1	3	0.5	0.5	145						1.0	0.1		0.1										6.10	7.62					1.52
4	1	4.0	7.5	140		0.0				1.0			0.1									B364700	7.62	9.14	**0.053**			VA05080696	1.52
5	1	6.0	16.0	150		0.0				1.0							3.0					B364701	9.14	10.67	**0.139**		Chromite (???); Pieces of quartz, no sulphides	VA05080696	1.53
1	1	2.0	3.0																			B364702	9.14	10.67	**0.061**	DUP		VA05080696	1.53
2	1	2.0	3.0																				10.67	12.19					1.52
1	1	3.0	3.0																				12.19	13.72					1.53
1	1	1.0	1.0																				13.72	25.24					11.52
2	1	1.5	3.0	20																			25.24	16.76					-8.48
1	1	0.5	0.5																				16.76	18.29					1.53
0																							18.29	19.81					1.52
1	1	2.0	2.0																				19.81	21.34					1.53
4	1	3.0	8.0	140		0.0				0.1												B364703	21.34	22.86	**0.038**			VA05080696	1.52
0																							22.86	23.78				-	0.92
2	1	1.0	2.0	130		0.0				0.0													23.78	24.38			Parallel to foliation		0.60
4	1	3.0	5.0	135		1.0	q/cb	3	2								5.0					B364704	24.38	25.91	**0.059**		Moly at edges	VA05080696	1.53
2	1	8.0	10.0	130						0.1													25.91	27.43					1.52
5	1	1.0	5.0	130	20	0.5	q/cb	4	3	0.1							0.1	4.0				B364705	27.43	28.56	**0.255**			VA05080696	1.13
																							28.56	29.91					1.35
																							29.91	30.48					0.57
1	4	2.0	2.0							4.0								5.0				B364706	30.48	32.00	**0.090**			VA05080696	1.52
5	1	4.0	14.0	30		0.0				0.1								3.0				B364707	32.00	33.53	**0.011**		Trace Magenetite(?)	VA05080696	1.53
4	1	15.0	23.0	30	40																	B364708	33.53	35.05	**0.014**			VA05080696	1.52
4	1	15.0	23.0	30	40																	B364709	33.53	35.05	**0.023**	PD/CA		VA05080696	1.52
																						B364710	STANDARD 1A		**0.917**	1A		VA05080696	
9	1	5.0	14.0	30															3.0			B364711	35.05	36.58	**0.008**			VA05080696	1.53
6	4	24.0	70.0							4.0							0.1	5.0				B364712	36.58	38.10	**0.006**		Hematite Stain	VA05080696	1.52
1	1	1.0	1.0	10		0.0																	38.10	39.62					1.52
1	1	1.0	1.0	50		1.0	cb	2	1														39.62	41.15					1.53
1	1	0.6	0.6	50		2.0	q	1									0.1					B364713	41.15	42.67	**0.007**			VA05080696	1.52
1	4	0.3	0.3	30		1.0	q	4	2											8.0									
0																							42.67	44.20					1.53
3	1	1.0	2.0	40		1.0	q/cb	3	1														44.20	45.72					1.52
3	1	1.0	3.0	40		0.0				0.0													45.72	47.24					1.52
																							47.24	47.92					0.68
1	3	0.3	0.3	30		2.0	cb/q	1	1								0.1					B364714	47.92	48.77	**0.022**			VA05080696	0.85
2	1	1.0	2.0	40		1.0	q	1															48.77	50.29					1.52
4	1	1.0	4.0	50	60	2.0	q/s	3		1.0								5.0					50.29	51.82					1.53
1	1	2.0	2.0	20		1.0	cb	2		0.1								5.0					51.82	53.34					1.52
1	1	1.0	1.0	30		0.5	cb	2		0.1								5.0					53.34	54.86					1.52
0																							54.86	56.53					1.67
3	1	1.0	3.0	40		2.0	q/cb	3		1.0									5.0			B364715	56.53	57.41	**0.006**			VA05080696	0.88
																						B364716	BLANK		**<0.005**			VA05080696	
1	1	2.0	2.0	45		2.0	q/cb	3		0.0													57.41	57.91					0.50
4	1	3.0	5.5	40		2.0	cb/q	4	0	0.1								5.0					57.91	59.44					1.53
4	1	2.0	7.0	40	20	q	q/s	2		0.1								5.0		5.0		B364717	59.44	60.48	**0.010**			VA05080696	1.04

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 3 of 10	
DRILL HOLE # : DG05-305C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
81		60.48	64.61	MSED: Predominantly (75%) 'bleached', silicified HFLS; Color light brown to grey; Still aphanitic and finely layered.	1	2			1	
81		64.61	76.20	MSED: Deep purple HFLS to smokey beige color with large quartz veins - up to 80cm; Within these veins are patches of micaceous materials appearing to be retrograded from HFLS patches. Some have metallic sheen. Evidence of shear from 75.5 - 76.2 m, quartz veins moved sinistrally.		1	1		1	
81		76.20	80.77	MSED: Slightly more carbonate veinlets, so rock is broken up, rare full diameter, pieces <10cm.		1		1	2	
81		80.77	84.69	MSED: More oxidized, whole section limonite infused along metased layers; Crumbly and medium brown.	4	2	0	2	2	
81		84.69	88.39	MSED: HFLS competent except 30 cm with extra carbonate.		1		1	1	
81		88.39	97.54	MSED: Oxidized and sheared HFLS from 88.39 - 92.96m; Pale grey-light brown HFLS to end of section; From 96.01 - 97.54m shear and clay alteration.	2	2		2	1	
81		97.54	99.27	MSED: Sericitized pale light brown/grey HFLS; Very broken up.	1	3		1		
10	99.27 - 102.11	99.27	102.11	GND: Highly clay altered; Color is greenish beige to white; GND texture barely distinguishable as quartz-eyes, no foliation.		3	2	3	1	
81	102.11 - 106.40	102.11	106.40	MSED: HFLS metased again; Last meter of section shows GND texture overprinted by HFLS foliation; Quartz veins still squished into foliation with beige-grey HFLS; Quartz-carb veins (noted) are similar to those in the GND dyke above.	2	2		1	2	
10	106.40 - 259.08	106.40	120.30	GND: Very crumbly and weak, carb-infused.		1	1	2	4	
10		120.30	132.59	GND: Somewhat more competent GND: Regular fracturing at 60° and 135° TCA; Alternating between very crumbly and broken and competent over 1-2m intervals.		3	2	2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2006

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides										Oxidation						Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scoordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
1	1	4.0	4.0	55		0.0				2.0			0.1					5.0					60.48	60.96			Disseminated clean, euhedral aspy (3 grains seen).		0.48
3	1	3.0	9.0	50	70	0.0																	60.96	62.48					1.52
0																							62.48	64.01					1.53
2	1	4.0	6.0	70		2.0	q	3	0	1.0			1.0					5.0				B364718	64.01	64.61	**0.170**			VA05080696	0.60
1	1	80.0	80.0	60		0.0											0.1			8.0		B364719	64.61	65.53	**0.009**			VA05080696	0.92
2	1	25.0	32.0	60	110	1.0	q	3															65.53	66.80					1.27
4	1	30.0	33.0	50	140	1.0	q/cb	3												8.0			66.80	68.00					1.20
0																							68.00	68.58					0.58
4	1	2.0	4.5	30	60					0.1								5.0					68.58	70.10					1.52
1	1	1.0	1.0	50		1.0	s/q/cb	4	1	10.0								2.0				B364720	70.10	71.63	**0.017**		Shiny massive and euh py	VA05080696	1.53
2	4	0.3	0.6	24																									
3	1	20.0	24.0	45		10.0	q/s/cb	2	0	4.0								4.0					71.63	73.15					1.52
0																							73.15	74.68					1.53
1	1	2.0	2.0							0.1								5.0					74.68	76.20					1.52
0																							76.20	77.72					1.52
1	1	2.0	2.0																				77.72	79.25					1.53
0																							79.25	80.77					1.52
0																							80.77	82.30					1.53
2	1	2.0	4.0	25		0.0																	82.30	83.83				-	1.53
4	1	4.0	9.0	50		0.0																	83.83	85.34					1.51
	1	1.0	2.0		0	q	4	0	0									5.0					85.34	86.87					1.53
4	1	3.0	7.0	40	50																		86.87	88.39					1.52
2	1	4.0	6.0	40		0.0				1.0								5.0					88.39	89.92					1.53
2	1	1.0	2.0	80	60	0.0				0.0													89.92	91.44					1.52
0																							91.44	92.96					1.52
1	1	2.0	2.0	60		0.0				5.0								3.0				B364721	92.96	94.15	**0.023**		Also diss py 1-2 cm from vein	VA05080696	1.19
1	3	1.0	1.0	50		1.0	cb	1		2.0								5.0											
1	1	2.0	2.0	60		0.0				5.0								3.0				B364722	92.96	94.15	**0.022**	DUP		VA05080696	1.19
1	3	1.0	1.0	50		1.0	cb	1		2.0								5.0											
0																							94.15	96.01					1.86
0																							96.01	97.54					1.53
3	1	1.0	3.0	50		0.0																	97.54	98.41					0.87
3	1	4.0	7.0	50	55	2.0	q/cb	4	0	4.0								5.0				B364723	98.41	99.27	**0.016**			VA05080696	0.86
3	1	0.5	1.5	10	55	0.0																B364724	99.27	100.58	**0.115**			VA05080696	1.31
2	3	0.5	1.0	50																		B364725	100.58	102.11	**0.075**			VA05080696	1.53
1	3	0.5	0.5	50						1.0								5.0				B364726	102.11	103.63	**0.054**			VA05080696	1.52
2	3	0.5	1.0	50						1.0												B364727	103.63	105.16	**0.013**			VA05080696	1.53
3	3	0.5	1.0	60		1.0	q	1														B364728	105.16	106.40	**0.051**			VA05080696	1.24
3	3	0.5	1.0	60		1.0	q	1														B364729	105.16	106.40	**0.042**	PD/CA		VA05080696	1.24
																						B364730	STANDARD 4D		**0.447**	4D		VA05080696	
3	1	1.0	2.0	61		0.0																B364731	106.40	107.54	**0.072**			VA05080696	1.14
2	1	1.0	2.0	70		20.0	q/s/cb	4		5.0								5.0				B364732	107.54	108.20	**0.084**			VA05080696	0.66
3	1	1.0	3.0	70						5.0								5.0				B364733	108.20	109.73	**0.065**			VA05080696	1.53
1	3	0.3	0.3	60		2.0	cb/s	4		1.0								5.0											
4	1	1.5	3.0	80		6.0	q/s/cb	4		4.0								5.0				B364734	109.73	111.25	**0.113**			VA05080696	1.52
1	6	0.5	0.5	40						100.0								5.0				B364735	111.25	112.78	**0.040**			VA05080696	1.53
																						B364736	BLANK		**<0.005**			VA05080696	
4	1	1.0	3.0	80						0.1								5.0				B364737	112.78	114.30	**0.203**			VA05080696	1.52
2	1	2.5	5.0	50							5.0											B364738	114.30	115.82	**0.171**		po-bt	VA05080696	1.52
1	1	1.5	1.5	50		1.0	q/s	3	0		3.0											B364739	115.82	116.33	**0.054**			VA05080696	0.51
3	1	1.0	2.0	80		2.0	cb/chl/s	4	0		3.0											B364740	116.33	117.35	**0.029**			VA05080696	1.02
3	1	1.0	3.0	60		2.0	q/cb	1			2.0											B364741	117.35	118.87	**0.090**			VA05082980	1.52
3	1	1.0	3.0	60		2.0	q/cb	1			2.0											B364742	117.35	118.87	**0.097**	DUP		VA05082980	1.52
1	6	0.3	0.3	60		2.0	cb/s/q	4		96.0			4.0					5.0				B364743	118.87	120.30	**0.201**		Flattened aspy	VA05082980	1.43
2	1	1.0	1.6	50		12.0	q/cb/s	5														B364744	120.30	121.50	**0.666**			VA05082980	1.20

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 5 of 10	
DRILL HOLE # : **DG05-305C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	GEOLOGICAL DESCRIPTION From:	To:	Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		132.59	146.30	GND: Somewhat broken up by crumbly carbonate infusion.		2	1	1	3	
10		146.30	153.92	GND: @147.25 - 147.83m, two 2cm quartz veins contain massive po; One vein contains more po than quartz; These are the only sulphide bearing zones in the 1.53m sample; Po-bearing quartz veins 1cm or less, continue through unaltered, competent GND.		1			1	
10		153.92	163.07	GND: Moderately infused with carbonate GND.	0	1	0	1	2	
10		163.07	167.64	GND continues but with much larger veins (up to 20cm), plus small ones ~1cm; Pyrrhotite is euhedral, in grains 2-3mm in diameter, and massive, in aggregates up to 2cm, often the full width of the vein. Magnetic.						
10		167.64	188.98	GND: Still unaltered GND; Quartz veins sheeted, smaller and with less mineralization of sulphides (4% po at most); Sulphides decrease to a minimum of 0-2% between 181 and 188m; Last interval has 2 veins with aspy, disseminated tiny grains (≤ 1mm) through vein and selvage. Half altered to scorodite.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
										Sulphides								Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	6.0	6.0	80						1.0								5.0				B364745	121.50	122.86	**0.389**		broken core	VA05082980	1.36
3	1	1.0	2.0	70	45	0.0				2.0	10.0									3.0		B364746	122.86	123.44	**0.019**			VA05082980	0.58
5	1	0.5	2.5	70	35						4.0									4.0		B364747	123.44	124.97	**0.018**			VA05082980	1.53
3	1	1.0	3.0	50		0.0					3.0		0.1							3.0		B364748	124.97	126.49	**0.064**			VA05082980	1.52
1	6	0.6	0.6	60		8.0	cb/q	5	0	100.0								5.0											
3	1	1.0	3.0	50		0.0					3.0		0.1							3.0		B364749	124.97	126.49	**0.060**	PD/CA		VA05082980	1.52
1	6	0.6	0.6	60		8.0	cb/q	5	0	100.0								5.0											
																						B364750	STANDARD 7G		**4.540**	7G		VA05082980	
4	1	1.5	4.6	40	80	1.0	q/s	3	0		5.0									2.0		B364751	126.49	128.02	**0.076**			VA05082980	1.53
3	1	12.0	23.0	50	70	30.0	cb/s/chl	4	0				9.0									B364752	128.02	129.54	**1.465**		Massive aspy at vn boundary	VA05082980	1.52
5	1	4.0	7.0	40		10.0	cb/s/chl	4			4.0		2.0									B364753	129.54	131.06	**0.088**			VA05082980	1.52
2	1	1.0	2.0	50		1.0	q/s	2			2.0											B364754	131.06	132.59	**0.137**			VA05082980	1.53
1	4	0.3	0.3	50		6.0	cb/s/chl	4		4.0								5.0	5.0										
5	1	3.0	7.5	55		1.0	q/cb	3			10.0	0.1			2.0							B364755	132.59	134.11	**0.066**			VA05082980	1.52
																						B364756	BLANK		**<0.005**			VA05082980	
6	1	3.0	6.0	50	20	1.0	cb/s	2			2.0									4.0		B364757	134.11	135.64	**0.171**			VA05082980	1.53
1	3	1.5	1.5	60		10.0	q	1																					
1	1	1.0	1.0	50		0.5	q	3			4.0								2.0	2.0		B364758	135.64	137.16	**0.058**			VA05082980	1.52
2	3	1.5	2.0	40		3.0	q/cb	4			15.0								5.0	2.0									
5	1	1.0	5.0	60		1.0	q	2			3.0									3.0		B364759	137.16	138.68	**0.042**			VA05082980	1.52
1	1	1.5	1.5	50		0.0					5.0											B364760	138.68	140.21	**0.065**			VA05082980	1.53
4	1	1.0	4.0	40		2.0	cb/s	4	0		6.0									1.0		B364761	140.21	141.73	**0.088**			VA05082980	1.52
4	1	1.0	4.0	40		2.0	cb/s	4	0		6.0									1.0		B364762	140.21	141.73	**0.393**	DUP		VA05082980	1.52
3	1	1.0	2.0	40		1.0	q	4			7.0									3.0		B364763	141.73	143.26	**0.100**			VA05082980	1.53
	1	1.0	2.0	40	30	1.0	q	4			10.0											B364764	143.26	144.78	**0.050**			VA05082980	1.52
2	1	1.5	3.0	30		1.0	q	4			5.0											B364765	144.78	146.30	**0.046**			VA05082980	1.52
2	6	2.0	4.0	60		4.0	q/cb/s	2			55.0											B364766	146.30	147.83	**0.235**			VA05082980	1.53
2	1	2.0	3.0	70		1.0																B364767	147.83	149.35	**0.050**			VA05082980	1.52
2	1	2.0	3.0	60		1.0	q/s	3	1		6.0									1.0		B364768	149.35	150.88	**2.060**			VA05082980	1.53
2	1	2.0	3.0	60		1.0	q/s	3	1		6.0									1.0		B364769	149.35	150.88	**0.072**	PD/CA		VA05082980	1.53
																						B364770	STANDARD 6F		**2.840**	6F		VA05082980	
4	1	1.0	2.0	60	20	1.0	q	3	0		5.0											B364771	150.88	152.40	**0.076**			VA05082980	1.52
4	1	1.0	3.0	25	50	1.0	q/cb/s	3	0		2.0		1.0									B364772	152.40	153.92	**0.803**			VA05082980	1.52
1	4	1.0	1.0	20		0.0				0.0												B364773	153.92	155.45	**0.125**			VA05082980	1.53
1	1	0.5	0.5	40		1.0	q/s	4														B364774	155.45	156.97	**0.021**			VA05082980	1.52
0																						B364775	156.97	158.50	**<0.005**			VA05082980	1.53
																						B364776	BLANK		**<0.005**			VA05082980	
1	1	1.0	1.0	50							3.0								4.0	1.0		B364777	158.50	160.02	**0.026**			VA05082980	1.52
1	1	2.0	2.0	50		2.0	q	4														B364778	160.02	161.54	**0.032**			VA05082980	1.52
2	1	1.0	2.0	40		2.0	q	4	0		10.0				1.0					1.0		B364779	161.54	163.07	**0.017**			VA05082980	1.53
3	1	20.0	22.5	25		15.0	cb/s/chl	5	0		3.0											B364780	163.07	164.59	**0.245**			VA05082980	1.52
3	1	14.0	24.0	35		10.0	cb/s/chl	5		1.0	8.0	3.0	0.1									B364781	164.59	165.18	**0.204**			VA05082980	0.59
3	1	14.0	24.0	35		10.0	cb/s/chl	5		1.0	8.0	3.0	0.1									B364782	164.59	165.18	**0.164**	DUP		VA05082980	0.59
4	1	2.0	6.0	25	15	1.0	q/cb	3				12.0	0.1									B364783	165.18	166.12	**0.313**			VA05082980	0.94
4	1	3.0	6.0	30		1.0	q/cb	2			2.0											B364784	166.12	167.64	**0.049**			VA05082980	1.52
4	1	1.0	3.5	40		10.0	cb/s/q/chl	5	0		3.0	0.1	7.0		1.0							B364785	167.64	169.03	**0.239**			VA05082980	1.39
4	1	1.0	3.2	40	50	2.0	q	2	0		1.0											B364786	169.03	170.69	**0.049**			VA05082980	1.66
3	4	0.3	1.1	70		20.0	cb/s	5	0																				
2	1	3.0	4.0	40		2.0	q/cb	5	0		2.0									2.0		B364787	170.69	172.21	**0.235**			VA05082980	1.52
5	1	4.0	7.0	40	25	1.0	q	3			2.0	0.1								2.0		B364788	172.21	173.74	**0.219**			VA05082980	1.53
5	1	4.0	7.0	40	25	1.0	q	3			2.0	0.1								2.0		B364789	172.21	173.74	**1.120**	PD/CA		VA05082980	1.53
																						B364790	STANDARD 2B		**2.970**	2B		VA05082980	
6	1	2.0	7.0	30	45																	B364791	173.74	175.26	**0.172**			VA05082980	1.52
4	1	1.2	3.6	50	25	1.0	q/cb	3			2.0											B364792	175.26	176.78	**0.075**			VA05082980	1.52
4	1	1.5	2.6	50	30	6.0	1/cb/s	4		1.0	4.0								1.0	1.0		B364793	176.78	178.31	**0.035**			VA05082980	1.53
4	1	1.0	3.5	30		1.0	q/cb	2			4.0									1.0		B364794	178.31	179.83	**0.067**			VA05082980	1.52
3	1	3.0	5.0	50		2.0	q/cb	1			1.0		10.0					2.0				B364795	179.83	181.36	**1.495**		Aspy conc at edges of one 3 cm vn.	VA05082980	1.53

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 1 of 10	
DRILL HOLE # : **DG05-305C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		188.98	205.21	GND: @ 190.5, 8cm of pure quartz (vein) is presenrved, but pebbles and lack of upper contact indicate some loss of recovery; From 190.9 to 193.3m is fault material; 40cm of brecciated quartz and GND within brown gouge material, followed by moderately re-arranged quartz veins (no selvage as all moved) black clay seams (veinlets) and slight brecciation all infused with carbonate. Two large quartz veins (18cm and 24cm) in the section, thickness unknown, assumed contacts @~50° TCA; Outside of this zone, the section is unaltered GND with sulphide-rich veins, occassional trace VG; Except from 201.07 - 201.78m, evidence of shear and limonite infusion, where rock is moderately broken up with limonite on faces.	1	2	1	1	2	
10		205.21	217.93	GND: Mostly (60%) moderately altered GND; Zones of carbonate (208.5 - 208.7m and 208.0 - 208.3m); Zone of limonite (209.5 - 210.8m); Zone of sericite (211.0 - 213.0m); Rest of unaltered GND with few quartz veins, not much mineralization.	2	2	1	0	2	
10		217.93	226.62	GND: Unaltered GND with quartz veins; Good mineralization but a lot of alteration within veins, po to bt and other minerals to chlorite; These are positioned within veins where sulphides are normally found.		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B364796	BLANK		<0.005			VA05082980	
2	1	1.0	2.0	30	0	1.0	q	2			0.1											B364797	181.36	182.88	0.043			VA05082980	1.52
3	1	1.2	3.0	40		1.0	q/s	2			2.0									4.0		B364798	182.88	184.40	0.036			VA05082980	1.52
2	1	0.8	1.3	50		0.5	q	4			2.0				1.0							B364799	184.40	185.93	0.185		VG?	VA05082980	1.53
2	1	1.0	2.0	30		2.0	q/s/cb	3			1.0									2.0		B364800	185.93	187.45	0.019			VA05082980	1.52
3	1	1.0	3.0	35	15	4.0	cb/s	5			1.0		2.0			0.1			2.0			B364801	187.45	188.98	0.200		Trace VG?	VA05082980	1.53
3	1	1.0	3.0	35	15	4.0	cb/s	5			1.0		2.0			0.1			2.0			B364802	187.45	188.98	0.338	DUP	Trace VG?	VA05082980	1.53
3	1	6.0	8.0	20	0	0.2	cb/s	3		2.0	8.0	2.0				0.1						B364803	188.98	189.73	1.320		Trace VG?	VA05082980	0.75
3	1	1.5	2.1	15	50	2.0	q/cb	3		3.0								5.0				B364804	189.73	190.50	2.500			VA05082980	0.77
4	1	8.0	11.0	60	30	2.0	q/s	4		4.0								3.0				B364805	190.50	192.02	2.190		Poor recovery	VA05082980	1.52
1	1	18.0	18.0	50		8.0	cb/s	3		5.0	2.0							5.0				B364806	192.02	192.37	5.890			VA05082980	0.35
3	1	3.0	6.5	50	20	0.0				10.0								2.0				B364807	192.37	192.85	2.590			VA05082980	0.48
2	1	24.0	30.0	40		4.0	s/q	3		7.0							1.0	3.0				B364808	192.85	193.69	19.300		moly	VA05082980	0.84
2	1	24.0	30.0	40		4.0	s/q	3		7.0							1.0	3.0				B364809	192.85	193.69	13.050	PD/CA		VA05082980	0.84
																						B364810	STANDARD 4D		0.427	4D		VA05082980	
1	1	6.0	6.0	20		8.0	q/cb/s	3		10.0	1.0	5.0										B364811	193.69	194.30	3.190		One veins continues into next sample	VA05082980	0.61
3	1	6.0	10.0	20	30	6.0	q/cb/s	3		5.0	3.0	4.0	2.0			0.1						B364812	194.30	195.07	8.960		Vein continues to this sample	VA05082980	0.77
2	1	15.0	16.0	20		10.0	q/cb/s	4			2.0	0.1										B364813	195.07	195.73	0.164			VA05082980	0.66
1	1	1.0	1.5	25	70	1.0	cb/q	4	0		3.0		0.1							10.0		B364814	195.73	196.60	0.172			VA05082980	0.87
2	1	1.5	2.5	25		3.0	q/s	4			1.0						0.1					B364815	196.60	198.12	0.134			VA05082980	1.52
																						B364816	BLANK		<0.005			VA05082980	
1	1	1.0	1.0	30		2.0	q/s	3			2.0		1.0						2.0			B364817	198.12	199.64	0.124			VA05082980	1.52
6	1	1.5	3.8	25	0	2.0	cb/q/s	4	0		6.0	0.1	0.1						2.0	5.0		B364818	199.64	201.07	0.308			VA05082980	1.43
1	1	2.0	2.0	10		2.0	q/s	2		2.0								5.0				B364819	201.07	201.78	0.307			VA05082980	0.71
1	4	0.3	0.3	40		8.0	cb/s	5														B364820	201.78	202.69	0.024			VA05082980	0.91
1	1	1.0	1.0	20		6.0	q/cb/s	4			3.0								3.0			B364821	202.69	204.22	0.189			VA05082980	1.53
1	3	1.0	1.0	35		4.0	q/cb/s	4																					
1	1	1.0	1.0	20		6.0	q/cb/s	4			3.0								3.0			B364822	202.69	204.22	0.071	DUP		VA05082980	1.53
1	3	1.0	1.0	35		4.0	q/cb/s	4																					
2	3	0.5	1.0	30	40	2.0	cb/chl	4			1.0		0.1						3.0			B364823	204.22	205.21	0.208			VA05082980	0.99
1	1	1.0	1.0	20		1.0	q/s/chl	3			10.0																		
4	1	10.0	13.0	25	15	10.0	s/cb/chl	5	3	4.0	2.0		1.0		1.0							B364824	205.21	205.74	0.553			VA05082980	0.53
3	1	2.0	4.0	30		10.0	cb/s	3	4	2.0								5.0				B364825	205.74	206.51	0.367			VA05082980	0.77
3	1	1.0	3.0	15							2.0		2.0						1.0	5.0		B364826	206.51	207.26	0.182			VA05082980	0.75
2	1	2.0	2.0	25		4.0	q/s	5		1.0						0.1		5.0				B364827	207.26	208.79	0.139			VA05082980	1.53
2	3	1.0	2.0	25		10.0	cb/s	3		2.0			0.1					5.0											
2	1	1.0	2.0	40	10	1.0	q	3		2.0	2.0							5.0		1.0		B364828	208.79	210.31	0.172			VA05082980	1.52
2	1	1.0	2.0	40	10	1.0	q	3		2.0	2.0							5.0		1.0		B364829	208.79	210.31	0.235	PD/CA		VA05082980	1.52
																						B364830	STANDARD 3C		0.090	3C		VA05082980	
2	3	1.0	3.0	20		4.0	q/s	3		5.0	3.0		0.1					5.0	2.0	3.0		B364831	210.31	211.84	0.943			VA05082980	1.53
1	6	0.3	0.3	10		10.0	cb/chl	3		100.0								5.0				B364832	211.84	213.26	0.111			VA05082980	1.42
3	1	1.0	3.0	20		1.0	q/s	2		3.0	3.0							3.0											
4	1	1.0	4.0	40	25	8.0	q/s	4	0		1.0									3.0		B364833	213.26	214.88	0.245			VA05082980	1.62
6	1	2.0	5.0	30	20	2.0	q/cb/s	4		5.0	3.0					1.0			2.0			B364834	214.88	216.41	0.368			VA05082980	1.53
5	1	2.0	5.0	35	25	4.0	q/cb/s	3	0	1.0	3.0	0.1										B364835	216.41	217.93	0.093			VA05082980	1.52
																						B364836	BLANK		<0.005			VA05082980	
1	1	4.0	4.0	20		10.0	cb/s	5	0													B364837	217.93	219.46	0.077			VA05082980	1.53
2	1	1.5	2.5	20		1.0	q	4	0		1.0		0.1						3.0	3.0		B364838	219.46	220.98	0.049			VA05082980	1.52
1	1	2.0	2.0	40		5.0	q/s	3	0	1.0	0.1							5.0				B364839	220.98	222.50	0.038			VA05082980	1.52
1	3	1.0	1.0	30		3.0	q/cb	4	0		5.0																		
2	1	0.5	1.0	20		1.0	q	3			2.0									3.0		B364840	222.50	224.03	0.126			VA05082980	1.53
4	1	1.0	3.3	60	15	1.0	q/s	4	0		2.0									3.0		B364841	224.03	225.55	0.093			VA05082980	1.52
4	1	1.0	3.3	60	15	1.0	q/s	4	0		2.0									3.0		B364842	224.03	225.55	0.063	DUP		VA05082980	1.52

DRILL LOG LEGEND P1	DATE: August 27 - Sept 1, 2005	PAGE 9 of 10	
DRILL HOLE # : DG05-305C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		226.62	244.14	GND: Moderately sheared GND: Most quartz veins are only partially present (some are moved/sheared) usually into ~30° TCA angle; Infusion of clay minerals and carbonate weaken rock; Between 237.74 - 239.27m, three quartz veins appear; 2 dark grey quartz veins at 5° TCA with carbonitic selvages (competent), as well as one milky quartz vein within the usual quartz/sericite selvage; @ 241.35m a 4cm concentration of fresh mafic minerals appears, generally at 40° TCA, includes bt, cpx, hb, ser; Last sample, 243.28 - 244.14m, is 75% rearranged, sheared; Quartz eyes within grey clay, trending with fine laminations at 70° TCA; Matrix of GND infused with sericite and carbonate; Clear boundary with next section, at 130° TCA.	1	3	1	2	3	
10		244.14	259.08	GND: Highly altered GND; One large quartz vein with 3 other large quartz veins in one 1m sample (251.46 - 252.00m) contains oxidized and unoxidized pyrite; Alteration pervasive across entire section, with yellowish green color, predominantly calcite and sericite; First three meters are black silicified GND with 2-10cm 'selvages' around microfractures - no vein, only selvage. Pale beige-green in color; All competent core except directly adjacent to largest quartz vein, where carbonitic clay infuses sericite-rich selvage to form gouge-clay for 10cm on either boundary.	1	4	1	1	3	
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: August 27 - September 1, 2005

LOGGED BY: M. STONE

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	20.0	23.5	40	25	4.0	q/s	3		4.0	8.0							1.0				B364843	225.55	226.62	**5.760**			VA05082980	1.07
							cb	1																					
1	1	1.0	1.0	40		0.0					0.1									6.0		B364844	226.62	228.14	**0.824**			VA05082980	1.52
3	1	4.0	8.5	40	50	2.0	q/cb	5	0	1.0	5.0	2.0						5.0				B364845	228.14	229.14	**0.928**			VA05082980	1.00
1	1		1.0	25		2.0	q/cb	2			0.1								2.0			B364846	229.14	230.12	**0.124**			VA05082980	0.98
3	1	1.0	2.5	25	60	3.0	q/cb	3		2.0	1.0							1.0		2.0		B364847	230.12	231.65	**0.861**			VA05082980	1.53
1	3	0.5	0.5	130		2.0	q/cb/s	4																					
5	1	1.0	3.6	30		2.0	q/s/cb	4			3.0											B364848	231.65	233.17	**0.189**			VA05082980	1.52
5	1	1.0	3.6	30		2.0	q/s/cb	4			3.0											B364849	231.65	233.17	**0.459**	PD/CA		VA05082980	1.52
																						B364850	STANDARD 5E		**1.505**	5E		VA05082980	
4	1	1.0	4.0	40	5	4.0	q/s	4		2.0	2.0							5.0				B364851	233.17	234.70	**0.459**			VA05082980	1.53
1	1	0.4	0.4	30		4.0	q/s	4			5.0									2.0		B364852	234.70	236.22	**0.287**			VA05082980	1.52
3	4	0.2	0.6	90	5	10.0	cb/s	5																					
2	1	1.0	2.0	20		2.0	q/cb	4			1.0											B364853	236.22	237.74	**0.121**		Grey quartz	VA05082980	1.52
3	1	1.5	35.0	5	20	6.0	q/cb	5		2.0	10.0	0.1										B364854	237.74	239.27	**0.421**		Dark grey quartz	VA05082980	1.53
						4.0	cb/s	4			3.0																Milky quartz		
3	1	0.5	1.5	15	30	4.0	cb/s	4		1.0	0.1						0.1					B364855	239.27	240.79	**1.310**		Moly	VA05082980	1.52
																						B364856	BLANK		**<0.005**			VA05082980	
4	1	1.0	4.0	20		2.0	cb/s	4		1.0	1.0							5.0		4.0		B364857	240.79	242.32	**0.521**			VA05082980	1.53
2	1	1.0	2.0	40		1.0	q	3			0.1								2.0			B364858	242.32	243.28	**0.043**			VA05082980	0.96
																						B364859	243.28	244.14	**0.144**			VA05082980	0.86
0																													
1	1	1.0	1.0	20		1.0	q/s	2		0.1	3.0							5.0				B364860	244.14	245.36	**0.418**			VA05082980	1.22
1	4	0.4	0.4	80		0.0				0.1								5.0											
4	1	1.0	4.0	25		6.0	s/chl/cb	5			8.0		2.0									B364861	245.36	246.89	**0.530**			VA05082980	1.53
4	1	1.0	4.0	25		6.0	s/chl/cb	5			8.0		2.0									B364862	245.36	246.89	**0.186**	DUP		VA05082980	1.53
5	1	0.3	1.5	20	45	0.0				2.0	10.0		2.0					5.0				B364863	246.89	248.41	**0.246**			VA05082980	1.52
2	1	1.5	3.0	60	25	4.0	q/cb/s	5		5.0								3.0				B364864	248.41	249.94	**0.371**			VA05082980	1.53
6	1	0.5	3.0	40	20	1.0	q/cb/s	5		1.0	2.0							5.0				B364865	249.94	251.46	**0.143**			VA05082980	1.52
4	1	25.0	34.0	70	25	10.0	cb/s	5	1	5.0								2.0				B364866	251.46	252.00	**0.728**			VA05082980	0.54
1	4	2.0	2.0	25		0.0				0.0																			
2	1	1.0	1.5	25	5	1.0	q/cb/s	3	1		1.0							2.0				B364867	252.00	252.98	**4.640**			VA05082980	0.98
2	1	1.0	2.0	30		2.0	q/s/cb	3			6.0											B364868	252.98	254.51	**0.053**			VA05082980	1.53
2	1	1.0	2.0	30		2.0	q/s/cb	3			6.0											B364869	252.98	254.51	**0.095**	PD/CA		VA05082980	1.53
																						B364870	STANDARD 2B		**2.960**	2B		VA05082980	
3	1	1.0	3.0	60	25					1.0								5.0				B364871	254.51	256.03	**0.069**			VA05082980	1.52
4	1	1.0	3.5	30		2.0	q/cb/s	3		2.0	2.0							5.0	2.0			B364872	256.03	257.56	**0.020**			VA05082980	1.53
3	1	0.5	1.3	25		4.0	q/cb/s	3		5.0								5.0				B364873	257.56	259.08	**0.150**			VA05082980	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-306C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1116m

BEARING: 000 | DIP: -50°

DATEs DRILLING: Aug 10-17, 2005

DATES LOGGING: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

CONTRACTOR: Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459954 NORTHING: 7099196

COORD SYSTEM: NAD 83: EASTING: 459834 NORTHING: 7099383

NAD 27 (CORRECTED for historic grid): EASTING: 459924 NORTHING: 7099206

SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 33 ft (10.06m)

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	10.06	Csg; No recovery
10.06	271.27	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B365317 - B365367

Requisition #: MASP448STRGOL.05Q Date Shipped: 9-Sept-05

Lab Record #: VA05080587 Date Received: 20-Sept-05

Sample Sequence: B365368 - B365547

Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Sept-05

Lab Record #: VA05083939 Date Received: 28-Sept-05

Duplicates:	365322; 365342; 365362; 365382; 365402; 365422; 365442; 365462; 365482; 365502; 365522; 365542
Preparation Duplicate/ Check Assay:	365329; 365349; 365369; 365389; 365409; 365429; 365449; 365469; 365489; 365509; 365529
Standards:	365330 (3C); 365350 (2B); 365370 (4D); 365390 (1A); 365410 (5E); 365430 (6F); 365450 (3C); 365470 (2B); 365490 (4D); 365510 (5E); 365530 (7G)
Blanks:	365336; 365356; 365376; 365396; 365416; 365436; 365456; 365476; 365496; 365516; 365536

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
60.96	335.9	-48.0	001.9	002.9
121.91	337.7	-48.9	003.7	004.7
182.87	337.2	-49.0	003.2	004.2
271.26	334.5	-48.2	000.5	001.5

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 1 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 10.06	0.00	10.06	Casing - No recovery						
10	10.06 - 271.27	10.06	19.81	GND: Unaltered portions of core is typical grey GND; Oxidation is pervasive throughout interval; Where previous alteration selvages occur, oxidation/limonite is much more intensive; Fractures/fracture faces contain calcite/carb and is also very limonitic; Siderite is common within fractures; Core is moderately broken up/fractured - 9cm average length with low angle fracturing (15-45°); Quartz veins contain vugs stained with limonite; Clay alteration occurs locally at 14 - 14.2m with dark rusty red-brown foliation at 45°; Unaltered GND from 17.9 - 18.25m (gradual contact).	4					
10		19.81	28.96	GND: GND is very clay altered and limonitic; full diameter core is rare, most core is extremely crumbly; Carbonate is present throughout core but not abundant; It's difficult to identify fracturing; No recovery from 21.34 - 22.86m.	4			5		
10		28.96	73.15	GND: GND is similar as previously described from interval 10.0 - 19.81m; @ 40.25m, a 0.4cm quartz vein contains blebs of a black massive, soft mineral with a black, slightly shiny, streak - possibly chalcocite?; It is common to see fresh fine grained speckled biotite on calcite fracture faces; Unaltered GND from 50.68 - 50.98m and 51.38 - 51.82m with fresh quartz veins (2% po); Intervals 59.44 - 60.96m (B365357) & 60.96 - 62.48m (B365358) are heavily fractured; Full diameter core is very rare; Limonite, calcite and speckled biotite on most faces.	3					

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval					
						Selvages				Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
3	1	0.6	1.1	45														2.0				B365317	10.00	10.67	1.315			VA05080587	0.67
2	1	1.2	1.6	45		0.3	q	5	4									4.0				B365318	10.67	12.19	0.186			VA05080587	1.52
4	1	0.6	2.0	40														2.0				B365319	12.19	13.72	0.112			VA05080587	1.53
3	1	0.5	1.3	50	40	0.3	q	5	4									2.0				B365320	13.72	15.24	0.091			VA05080587	1.52
4	1	0.7	1.4	45		1.0	q	5	4									5.0				B365321	15.24	16.76	0.071			VA05080587	1.52
4	1	0.7	1.4	45		1.0	q	5	4									5.0				B365322	15.24	16.76	0.070	DUP		VA05080587	1.52
3	1	1.2	2.8	45		1.0	q	3	4									5.0				B365323	16.76	18.29	0.022			VA05080587	1.53
0																						B365324	18.29	19.81	0.138			VA05080587	1.52
0																						B365325	19.81	21.34	0.013			VA05080587	1.53
0																						B365326	21.34	24.38	0.014			VA05080587	3.04
2	1	0.5	0.7	60														2.0				B365327	24.38	25.91	0.022			VA05080587	1.53
0																						B365328	25.91	27.43	0.071			VA05080587	1.52
0																						B365329	25.91	27.43	0.169	PD/CA		VA05080587	1.52
																						B365330	STANDARD 3C		0.091	3C		VA05080587	
0																						B365331	27.43	28.96	0.358			VA05080587	1.53
3	1	0.5	1.5	45		0.3	q	5	4									2.0				B365332	28.96	30.48	0.044			VA05080587	1.52
5	1	0.7	2.0	45	60	0.5	q	5	4				0.1					4.0				B365333	30.48	32.00	0.515			VA05080587	1.52
4	1	0.4	1.6	45	60	0.3	q	5	4									5.0				B365334	32.00	33.53	0.109			VA05080587	1.53
4	1	0.5	1.2	30		0.3	q	5	4									5.0				B365335	33.53	35.05	0.088			VA05080587	1.52
																						B365336	BLANK		<0.005			VA05080587	
3	1	0.4	0.4	40		0.3	q	5	3									2.0				B365337	35.05	36.58	0.331			VA05080587	1.53
3	1	0.4	1.2			0.2	q	5	3	0.1								2.0				B365338	36.58	38.10	0.717			VA05080587	1.52
1	1	0.6	0.6	40														5.0				B365339	38.10	39.62	0.439			VA05080587	1.52
5	1	0.7	2.4	40		0.3	q	5	3		0.1		0.1				1.0	5.0				B365340	39.62	41.15	0.175		Chalcocite	VA05080587	1.53
6	1	0.6	30.0	55		0.3	q	5	4		0.1							10.0				B365341	41.15	42.67	0.290			VA05080587	1.52
6	1	0.6	30.0	55		0.3	q	5	4		0.1							10.0				B365342	41.15	42.67	0.137	DUP		VA05080587	1.52
5	1	0.5	1.6	30		0.3	q	4	2									5.0				B365343	42.67	44.20	0.171			VA05080587	1.53
4	1	1.0	2.2	30	60	0.3	q	5	4				0.1				1.0	5.0				B365344	44.20	45.72	0.373		Chalcocite	VA05080587	1.52
2	1	0.6	0.8	30		0.3	q	5	3								0.1					B365345	45.72	47.24	0.106		Chalcocite	VA05080587	1.52
2	1	0.4	0.7	30	60													2.0				B365346	47.24	48.77	0.050			VA05080587	1.53
5	1	0.6	18.0	30									0.1				0.1					B365347	48.77	50.29	0.082			VA05080587	1.52
4	1	0.3	1.1	30	40						2.0											B365348	50.29	51.82	0.065			VA05080587	1.53
4	1	0.3	1.1	30	40						2.0											B365349	50.29	51.82	0.092	PD/CA		VA05080587	1.53
																						B365350	STANDARD 2B		3.090	2B		VA05080587	
3	1	0.5	1.2	30							0.1							4.0				B365351	51.82	53.34	0.103			VA05080587	1.52
1	1	0.3	0.3	35														2.0				B365352	53.34	54.86	0.023			VA05080587	1.52
0																						B365353	54.86	56.39	0.054			VA05080587	1.53
3	1	1.0	2.2	30														2.0				B365354	56.39	57.91	0.023			VA05080587	1.52
1	1	0.4	0.4	45									0.1					2.0				B365355	57.91	59.44	0.100			VA05080587	1.53
																						B365356	BLANK		<0.005			VA05080587	
2	1	0.2	0.4	30	45												0.1	2.0				B365357	59.44	60.96	0.034		Chalcocite?	VA05080587	1.52
0																						B365358	60.96	62.48	0.040			VA05080587	1.52
2	1	0.4	0.8	40														2.0				B365359	62.48	64.01	0.041			VA05080587	1.53
1	1	0.6	0.6	40													0.1	2.0				B365360	64.01	65.53	0.024			VA05080587	1.52
1	3	0.3	0.3	40																									
0																						B365361	65.53	67.06	0.060			VA05080587	1.53
0																						B365362	65.53	67.06	0.019	DUP		VA05080587	1.53

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 3 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		73.15	88.39	GND: GND similar to previous, except GND is more heavily fractured; Broken blocks are angular with an average size of 5x3x3cm; Random blocks of full diameter core up to 15cm; Slickenlines: @81.27m face at 40° with lines at 40°; @ 85.30m 55°/65° TCA.	3					
10		88.39	92.96	GND: GND is relatively unaltered, minor limonite occurs locally throughout core in intervals up to 25cm; Limonite is also present where local quartz flooding occurs (silicified core); Limonitic interval contacts are gradual (rarely sharp): GND is competent.	1					
10		92.96	108.82	GND: GND is same as previously described in interval 10.0 - 19.81m; From 100.45 - 100.55m core is extremely carb altered and clay alt'd and very limonitic; Slickenlines: @ 94.38m = 2°/60° TCA; @ 106.6m broken, angular clocks of MSED occur. Thickness of MSED cannot be determined (<25cm); Various blocks show a sharp contact with GND at 15°-20°. MSED consists of black and light brown bedding/foliation.	3					
10		108.82	118.87	GND: GND similar to previous from intervals 88.39 - 92.96m	2					
10		118.87	125.21	GND: GND has been intensely sericite altered and oxidized; Locally core has been very clay altered as well; Where sericite and clay alteration is most intense, carbonate alteration is also strong; Core appears brecciated from 119.38 - 119.55m with abundant angular white quartz clasts (1x.5x.5cm avg); Brecciation has sharp up hole contact with white quartz vein (3.5cm) and shear zone at 30° TCA; Breccia matrix is very limonitic with abundant smaller quartz clasts (2x2x3mm avg), no carb alteration is observed; Shear zone contains major elongate v f gr massive pyrite along foliation at 20° and 60° TCA; Matrix consists of small quartz eyes (2x2x2mm) and sericitized GND; Throughout SHEAR ZONE are large vugs (up to 3x3x1.5cm) stained with limonite, perhaps due to brecciation or oxidation of sulphides.	5	5				

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n

Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
2	1	0.4	0.4	40														2.0				B365363	67.06	68.58	0.057			VA05080587	1.52
2	1	0.6	1.2	40														3.0				B365364	68.58	70.10	0.030			VA05080587	1.52
4	1	0.4	1.1	60	30	0.4	s	5	4				0.1					5.0				B365365	70.10	71.63	0.221			VA05080587	1.53
0																						B365366	71.63	73.15	0.056			VA05080587	1.52
2	1	0.5	1.0	45														1.0				B365367	73.15	74.68	0.031			VA05080587	1.53
1	1	0.5	0.5	45														4.0				B365368	74.68	76.20	0.023			VA05083939	1.52
1	1	0.5	0.5	45														4.0				B365369	74.68	76.20	0.033	PD/CA		VA05083939	1.52
																						B365370	STANDARD 4D		0.451	4D		VA05083939	
0																						B365371	76.20	77.72	0.025			VA05083939	1.52
0																						B365372	77.72	79.25	0.009			VA05083939	1.53
1	1	0.5	0.5	45														2.0				B365373	79.25	80.77	0.022			VA05083939	1.52
1	1	0.4	0.4	45														2.0				B365374	80.77	82.30	0.024			VA05083939	1.53
1	1	0.4	0.4	40														2.0				B365375	82.30	83.82	0.019			VA05083939	1.52
																						B365376	BLANK		<0.005			VA05083939	
1	1	0.4	0.4	45														5.0				B365377	83.82	85.34	0.025			VA05083939	1.52
0																						B365378	85.34	86.87	0.028			VA05083939	1.53
1	1	0.2	0.2	45														2.0				B365379	86.87	88.39	0.018			VA05083939	1.52
3	1	0.5	1.2	45		0.2	q	5	3	10.0												B365380	88.39	89.92	0.814			VA05083939	1.53
1	1	0.4	0.4	45		0.4	s	3	1									1.0				B365381	89.92	91.44	0.022			VA05083939	1.52
1	1	0.4	0.4	45		0.4	s	3	1									1.0				B365382	89.92	91.44	0.043	DUP		VA05083939	1.52
0																						B365383	91.44	92.96	0.025			VA05083939	1.52
2	1	1.0	1.5	45														5.0				B365384	92.96	94.49	0.077			VA05083939	1.53
0																						B365385	94.49	96.01	0.025			VA05083939	1.52
0																						B365386	96.01	97.54	0.096			VA05083939	1.53
3	1	0.4	1.1	30	45								0.1					2.0				B365387	97.54	99.06	0.189			VA05083939	1.52
1	1	0.3	0.3	30		0.2	q	5	4									1.0				B365388	99.06	100.58	0.479			VA05083939	1.52
1	1	0.3	0.3	30		0.2	q	5	4									1.0				B365389	99.06	100.58	0.298	PD/CA		VA05083939	1.52
																						B365390	STANDARD 1A		0.957	1A		VA05083939	
1	1	0.4	0.4	40																		B365391	100.58	102.11	0.047			VA05083939	1.53
3	1	1.0	2.5	60	30	0.3	q	5	3									2.0				B365392	102.11	103.63	0.147			VA05083939	1.52
0																						B365393	103.63	105.16	0.085			VA05083939	1.53
1	1	1.5	1.5	60														2.0				B365394	105.16	106.68	0.019			VA05083939	1.52
2	1	0.3	0.6	60	30								1.0					2.0				B365395	106.68	108.20	0.031			VA05083939	1.52
																						B365396	BLANK		<0.005			VA05083939	
2	1	1.0	2.0	30		0.3	q	5	3									2.0				B365397	108.20	108.82	0.034			VA05083939	0.62
2	5	0.3	0.5	45	30	0.4	q	3	2													B365398	108.82	109.73	0.039			VA05083939	0.91
1	1	0.2	0.2	45		0.3	q	5			5.0																		
4	1	0.4	1.2	45	30						1.0	0.1	0.1					2.0				B365399	109.73	111.25	0.108			VA05083939	1.52
1	1	1.0	1.0	45																		B365400	111.25	112.78	0.029			VA05083939	1.53
1	5	0.3	0.3	40																									
6	1	1.2	2.8	60	40	0.4	q	5	3				0.1					2.0				B365401	112.78	114.30	0.093			VA05083939	1.52
6	1	1.2	2.8	60	40	0.4	q	5	3				0.1					2.0				B365402	112.78	114.30	0.038	DUP		VA05083939	1.52
1	1	1.0	1.0	40		0.3	q	5			2.0											B365403	114.30	115.82	0.213			VA05083939	1.52
4	1	1.0	1.8	30	45						1.0		1.0					1.0				B365404	115.82	117.35	0.021			VA05083939	1.53
4	1	1.0	2.6	30							1.0							2.0				B365405	117.35	118.87	0.225			VA05083939	1.52
0																						B365406	118.87	119.34	0.074			VA05083939	0.47

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 5 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.21	131.06	GND: Unaltered GND with slight oxidation, same as described from interval 88.39 - 92.96m; Slickenlines: @130.9m = face at 30° and lines at 60°.	1					
10		131.06	143.26	GND: GND is moderately clay altered through out most of the interval; Oxidation is pervasive throughout as well; Core appears much lighter in colour; Core is heavily fractured from 131.06 - 132.15m and 140.21 - 141.3m; Clay alteration tends to be more intense where core is heavily fractured; Quartz veining still commonly vuggy and stained with limonite; @ 140.4m minor shear zone (~5cm) with foliation at 20°. Shear zone consists of sericite altered matrix with small quartz eyes (2x2x2mm) and massive, black, clayey pyrite.	4			3		
10		143.26	156.97	GND: Unaltered God same as previously described from 88.39 - 92.96m; Oxidation only along fractures/fracture faces except locally at 148.86 - 149.35m where GND is moderately oxidized throughout; From 153.01 - 153.76m GND is moderately clay altered (3) and paler; Abundant calcitic fractures throughout; Evidence of quartz veining but veins too broken/irregular to measure; No foliation. Slickenlines: @149.33m face at 30° with lines at 45°; @ 150.8m 30°/45°; @ 151.65m 60°/75° TCA.	1					
10		156.97	163.07	GND: Unaltered grey GND; Rare limonite on fractures; Fracture faces/fills still contain calcite but now seeing sericite selvages up to 8cm (non-oxidized); Fracture faces also have darker green mineral (chl?) with calcite; Quartz veining becoming more abundant; @ 157.08m, 0.8cm quartz vein displays 2.5cm sinistral displacement by calcite filled fractures; Slickenlines: @158.48m, face at 20° with lines at 30° TCA; @ 159.05m, face at 30° with lines at 60°; @ 159.45m, face at 2° with lines at 45° TCA.						

DRILL LOG LEGEND P2

Selvages: 0 = No Alteration; 5 = Intense Alt'n
Ox. State: 0 = No Oxidized Sulphides; 5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	3.5	3.5	30									5.0									B365407	119.34	119.69	**33.800**			VA05083939	0.35
1	1	0.4	0.4	30																		B365408	119.69	120.40	**0.052**			VA05083939	0.71
1	1	0.4	0.4	30																		B365409	119.69	120.40	**0.048**	PD/CA		VA05083939	0.71
																						B365410	STANDARD 5E		**1.495**	5E		VA05083939	
3	1	1.2	2.2	30						1.0												B365411	120.40	121.92	**0.045**			VA05083939	1.52
2	1	9.0	9.5	50						2.0								1.0				B365412	121.92	123.44	**0.095**			VA05083939	1.52
3	1	1.0	1.6	25									0.1					2.0				B365413	123.44	125.21	**0.074**			VA05083939	1.77
2	1	1.4	2.4	25														1.0				B365414	125.21	126.49	**0.034**			VA05083939	1.28
1	1	0.5	0.5	30														1.0				B365415	126.49	128.02	**0.047**			VA05083939	1.53
																						B365416	BLANK		**<0.005**			VA05083939	
4	1	0.5	1.8	30						1.0	1.0											B365417	128.02	129.54	**0.010**			VA05083939	1.52
4	1	0.7	1.7	30							5.0	0.1	1.0									B365418	129.54	131.06	**0.045**			VA05083939	1.52
2	1	1.0	1.5	40														1.0				B365419	131.06	132.59	**0.058**			VA05083939	1.53
2	1	1.0	2.0	30														1.0				B365420	132.59	134.11	**0.141**			VA05083939	1.52
1	6	0.5	0.5	10						90.0																			
4	1	3.5	5.0	30	60													1.0				B365421	134.11	135.64	**0.090**			VA05083939	1.53
4	1	3.5	5.0	30	60													1.0				B365422	134.11	135.64	**0.177**	DUP		VA05083939	1.53
2	1	0.8	1.4	30														1.0				B365423	135.64	137.16	**0.060**			VA05083939	1.52
3	1	1.2	2.2	30	45													2.0				B365424	137.16	138.68	**0.208**			VA05083939	1.52
1	1	0.4	0.4	30														1.0				B365425	138.68	140.21	**0.027**			VA05083939	1.53
0																						B365426	140.21	141.73	**0.483**			VA05083939	1.52
1	1	1.0	1.0	30																		B365427	141.73	143.26	**0.035**			VA05083939	1.53
4	1	1.7	4.1	30	45						1.0		0.1					1.0				B365428	143.26	144.78	**0.035**			VA05083939	1.52
4	1	1.7	4.1	30	45						1.0		0.1					1.0				B365429	143.26	144.78	**0.042**	PD/CA		VA05083939	1.52
																						B365430	STANDARD 6F		**2.810**	6F		VA05083939	
4	1	0.5	1.5	30							1.0		1.0				1.0					B365431	144.78	146.30	**0.074**		Calcite?	VA05083939	1.52
2	1	0.5	0.8	30		0.2	q/s	4	1		1.0		1.0									B365432	146.30	147.83	**0.086**			VA05083939	1.53
5	1	0.5	2.0	30		0.4	q/s	5	2		1.0	0.1	2.0									B365433	147.83	149.35	**0.099**			VA05083939	1.52
5	1	2.5	3.6	30	40	0.5	q/s	5	2	10.0	1.0	0.1	4.0									B365434	149.35	150.88	**0.185**			VA05083939	1.53
1	1	0.2	0.2	40	40	0.2	q/s	5	0		0.1											B365435	150.88	152.40	**0.018**			VA05083939	1.52
1	5	0.2	0.2	30	30								5.0																
																						B365436	BLANK		**<0.005**			VA05083939	
																						B365437	152.40	153.01	**0.016**			VA05083939	0.61
0																						B365438	153.01	153.76	**0.162**			VA05083939	0.75
0																						B365439	153.76	155.45	**0.269**			VA05083939	1.69
2	1	2.0	2.5	45	30						0.1																		
2	5	0.4	0.7	40							2.0		2.0																
1	1	0.5	0.5	45																		B365440	155.45	156.97	**0.642**			VA05083939	1.52
1	6	0.4	0.4	40		0.5	q	4					40.0																
7	1	0.8	2.8	30	40	0.3	q	5		2.0	5.0	0.1	2.0									B365441	156.97	158.50	**0.133**		QV with py is within ser frac selvage	VA05083939	1.53
1	6	0.2	0.2	40		0.5	q	5			20.0		2.0																
7	1	0.8	2.8	30	40	0.3	q	5		2.0	5.0	0.1	2.0									B365442	156.97	158.50	**0.182**	DUP	QV with py is within ser frac selvage	VA05083939	1.53
1	6	0.2	0.2	40		0.5	q	5			20.0		2.0																
1	1	0.6	0.6	60							1.0	0.1	2.0									B365443	158.50	160.02	**0.023**			VA05083939	1.52
1	1	1.5	1.5	35						1.0	1.0											B365444	160.02	161.54	**17.200**		QV has 1mm envelope of cb/chl	VA05083939	1.52
5	1	0.5	2.5	35		1.0	s	4			2.0		1.0									B365445	161.54	163.07	**0.144**			VA05083939	1.53

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 7 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		163.07	170.69	GND: Grey GND is softer and slightly lighter in colour due to clay alteration; For the most part, core is competent except locally where it is moderately oxidized and heavily fractured with carb/calcite filled fracts from 164.59 - 165.65m and 166.52 167.64m; Shear zones tend to be more intensely clay altered and have dull grey clay zones along the foliation; Quartz eyes within shear zones are brittle and slightly softer; Shear zones: @163.37 - 163.42m at 50°; @ 164.08 - 164.17m at 70°; @ 167.8 - 167.90m at 35°; Dull grey clay stringers (whitish streaks) commonly contain v f gr py disseminated throughout; Slickenlines: @166.15m face at 40° with lines at 45°; @ 167.0m face at 10° with lines at 60°; @ 168.0m face at 30° with lines at 45° TCA.				3		
10		170.69	178.50	GND; GND is only slightly clay altered, slightly lighter grey than grey GND; Calcite fill fractures throughout; Limonitic fractures approx 60%, decreasing down hole; Intense clay alteration occurs locally from 175.2 - 175.36m and 178.25 - 178.38m; <1mm veinlets consisting of chlorite and carbonate are common with po, and at various angles; Slickenlines: @ 174.45m face at 5° with lines at 1°; @ 175.56m face at 30° with lines at 40° TCA.				1		
10		178.50	190.50	GND: Unaltered GND with small intervals of sericite alteration; Same as previously described (156.97 - 163.07m), though no limonite on fractures; Smeared pyrite common along slip faces; Slickenlines: @ 179.7m, face at 15° with lines at 15°; @ @ 182.38m face at 60° with lines at 2°; @ 182.4m face at 30° with lines at 40°; @ 186.05m face at 30° with lines at 45°; @ 186.68m face at 45° with lines at 5° TCA.						
10		190.50	198.12	GND: GND has undergone chlorite and sericite alteration; Sericite alteration is more abundant throughout intervals; Sections of only slight sericite alteration occur from 194.36 - 195.0m and 195.0 - 195.42m; Chlorite alteration is most abundant up hole; Where only sericite alteration occurs, euh-subhed grains of k-spar (up to 4x2.5mm) are speckaled throughout as well as <1mm veinlets of k-spar; From 190.5 - 191.07m (B365472), 2 quartz veins occur...one thick (>10cm) white with down ctc at 45° TCA, containing fine to med gr euhedral pyrite; Other vein 1.8cm thick, containing abundant v f gr massive py as stringers and blebs throughout; Minor SHEAR ZONE/FAULT GOUGE at 193.29m at 70° TCA (1.5cm); @ 197.95m, 2 quartz veins at 80° are offset 1cm by a dextral motion by 5° fracture containing v f gr py; Slickenlines: @ 194.3m, face at 20° with lines at 50° TCA; @ 196.9m, face at 70° with lines at 2°; @ 197.05m face at 80° with lines at 90° TCA.		5	3			3

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	5	0.3	0.3	35		0.5	q	5			5.0																		
0																						B365446	163.07	164.59	**0.309**			VA05083939	1.52
2	1	2.5	4.6	50						1.0			0.1					1.0				B365447	164.59	165.65	**0.119**			VA05083939	1.06
1	1	0.7	0.7	50						1.0								1.0				B365448	165.65	166.52	**0.140**			VA05083939	0.87
1	1	0.7	0.7	50						1.0								1.0				B365449	165.65	166.52	**0.038**	PD/CA		VA05083939	0.87
																						B365450	STANDARD 3C		**0.101**	3C		VA05083939	
0																						B365451	166.52	167.64	**0.085**			VA05083939	1.12
2	1	0.6	1.2	30	45																	B365452	167.64	169.16	**0.787**			VA05083939	1.52
2	1	2.0	3.0	65																		B365453	169.16	170.69	**0.063**			VA05083939	1.53
3	1	1.0	2.0	35		0.6	q	5		3.0	4.0	0.1	2.0									B365454	170.69	172.21	**0.313**			VA05083939	1.52
1	1	0.4	0.4	35							10.0	2.0										B365455	172.21	173.74	**0.023**			VA05083939	1.53
																						B365456	BLANK		**<0.005**			VA05083939	
0																						B365457	173.74	174.86	**0.029**			VA05083939	1.12
0																						B365458	174.86	175.49	**0.983**			VA05083939	0.63
1	1	0.5	0.5	50																		B365459	175.49	177.05	**0.330**			VA05083939	1.56
4	1	0.8	2.2	30		2.0	q/chl	4		0.1	3.0											B365460	177.05	178.50	**0.065**		Py found in cb bleb within QV	VA05083939	1.45
1	1	0.4	0.4	35							1.0											B365461	178.50	179.83	**0.097**			VA05083939	1.33
1	1	0.4	0.4	35							1.0											B365462	178.50	179.83	**0.066**	DUP		VA05083939	1.33
1	1	0.2	0.2	35							1.0											B365463	179.83	181.36	**0.030**			VA05083939	1.53
4	1	0.5	2.0	40						1.0	2.0											B365464	181.36	182.88	**0.200**			VA05083939	1.52
1	6	0.4	0.4			0.3	q	5			15.0																		
0																						B365465	182.88	184.40	**0.357**			VA05083939	1.52
1	1	0.4	0.4	35							1.0											B365466	184.40	185.93	**0.010**			VA05083939	1.53
1	1	0.4	0.4	40							2.0											B365467	185.93	187.45	**0.063**			VA05083939	1.52
3	1	0.8	1.8	40	45						1.0	0.1										B365468	187.45	188.98	**0.047**			VA05083939	1.53
3	1	0.8	1.8	40	45						1.0	0.1										B365469	187.45	188.98	**0.053**	PD/CA		VA05083939	1.53
																						B365470	STANDARD 2B		**3.180**	2B		VA05083939	
1	1	0.4	0.4	40							1.0											B365471	188.98	190.50	**0.113**			VA05083939	1.52
2	1	10.0	11.8	45						5.0			1.0									B365472	190.50	191.07	**5.000**			VA05083939	0.57
2	1	0.4	0.8	30						0.1	2.0											B365473	191.07	192.02	**0.239**			VA05083939	0.95
2	1	1.2	1.7	60	30						3.0											B365474	192.02	193.55	**0.051**			VA05083939	1.53
4	1	0.5	1.2	40	10					0.1	2.0											B365475	193.55	195.07	**0.174**			VA05083939	1.52
																						B365476	BLANK		**<0.005**			VA05083939	
6	1	0.5	2.5	35						1.0	2.0											B365477	195.07	196.60	**0.662**			VA05083939	1.53
1	6	0.4	0.4	30						2.0	15.0																		
4	1	1.0	2.8	15	80					1.0	2.0											B365478	196.60	198.12	**0.190**			VA05083939	1.52

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 9 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		198.12	203.60	GND: GND is slightly sericite altered throughout; Clay alteration gradually increases downhole (1 to 2); A 4cm white quartz vein (@ 30° TCA) is displaced at 201.28m (40°), 201.45m (40°) and 201.62m (70°); @ 201.62m dextral displacement is measured to be 6cm at 70° with 0.8cm fault gg; @ 199.6m, a 3cm white quartz vein with large massive pyrrhotite blebs (4x2cm); Slickenlines: @199.54m the fracture face is at 60° with lines at 90° TCA: @ 200.00m the face is at 1° with lines at 1°.		2		1		
10		203.60	211.84	GND: Core is highly clay altered, moderately sericite altered, and locally clay altered (with more intense clay alteration); @ 203.6 - 205.74m = SHEAR ZONE with low angle foliations (10° - 30° and 60°), containing angular quartz veins clasts (white) up to 3x3cm. Also abundant small quartz eyes throughout, soft sericitized, clay altered matrix with carbonate; Quartz vein in shear zone displaced and broken up; Slickenlines: @ 205.5m, face at 5° with lines at 30°; @ 210.85m face at 30° with lines at 85°.		3		5	3	
10		211.84	224.03	GND: GND is intensely sericite altered as previous interval but clay alteration is less extensive (intervals up to 40cm); Where clay alteration is most intensive, carb alteration occurs (small gm-gy clay); Massive py from 220.61 - 220.72m; From 221.38 - 221.82m core appears brecciated with white quartz vein clasts and irregular/displaced quartz veins. Fine to med gr euhedral py is disseminated throughout; K-spar grains (eu-subhed) and vnlts throughout tend to be softer and slightly carb alt'd; K-spar veinlets and euhedral, speckled grains become more abundant down hole; Slickenlines: @212.39m - face at 45° with lines at 5°; @ 212.8m face at 45° with lines at 85°.		5		3		
10		224.03	258.52	GND: Slight ser alteration; Locally, intense sericite alteration with euh-subhed k-spar grains and vnlts (228.6 - 228.86m, 229.3 - 229.45m, 232.7 - 233.0m, 234.75 - 235.35m, 239.27 - 239.94m, 244.37 - 245.71m - 247.47 - 247.91m and 250.18 - 259.41m); Fracture faces are chl/ser altered with carb/calcite; From 235.15 - 235.35m sericite core appears brecciated; Core is competent with abnt k-spar vnlts (mm to 1.7cm); Fine - C gr py blebs also abndt (~15%); Large massive spy bleb (2.5x1cm) present (~5% of breccia zone); Breccia zone has sharp contact with 70% f gr py and 20% k-spar; From 240.4 - 240.94m MGD is present with sharp contact to unaltered grey GND at 5° TCA; Slickenlines: @233.2 = 40°/80°; @ 233.3m = 70°/5°; @ 235.17m = 80°/5°; @ 240.25m = 20°/75°; @ 245.6m = 80°/5°; @ 246.49m = 45°/45°; @ 248.2m = 30°/90°; @ 249.3m = 40°/75°; @ 249.42m = 5°/60°; @ 249.42m = 85°/85° TCA.						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
5	1	3.0	5.8	60	45					0.1	5.0											B365479	198.12	199.64	1.040			VA05083939	1.52
4	1	0.8	2.4	60							1.0											B365480	199.64	201.17	0.286			VA05083939	1.53
2	1	4.0	6.0	30	15					1.0	2.0											B365481	201.17	202.30	0.153			VA05083939	1.13
2	1	4.0	6.0	30	15					1.0	2.0											B365482	201.17	202.30	0.105	DUP		VA05083939	1.13
1	1	0.3	0.3	60							2.0											B365483	202.30	203.60	0.231			VA05083939	1.30
3	1	1.0	3.0	60																		B365484	203.60	204.22	0.064			VA05083939	0.62
0																						B365485	204.22	205.74	1.010			VA05083939	1.52
2	1	0.5	0.8	15	60					2.0												B365486	205.74	207.26	0.559			VA05083939	1.52
0																						B365487	207.26	208.79	0.400			VA05083939	1.53
1	1	0.4	0.4	60							1.0											B365488	208.79	210.31	0.060			VA05083939	1.52
1	1	0.4	0.4	60							1.0											B365489	208.79	210.31	0.049	PD/CA		VA05083939	1.52
																						B365490	STANDARD 4D		0.444	4D		VA05083939	
0																						B365491	210.31	211.48	0.024			VA05083939	1.17
3	1	1.5	2.2	60	45					1.0	1.0											B365492	211.48	213.36	0.142			VA05083939	1.88
1	1	1.2	1.2	60						3.0												B365493	213.36	214.88	0.163			VA05083939	1.52
1	1	0.4	0.4	60							2.0											B365494	214.88	216.41	0.136			VA05083939	1.53
1	3	0.3	0.3	60																									
2	1	0.2	0.4	60							2.0											B365495	216.41	217.93	0.111			VA05083939	1.52
																						B365496	BLANK		<0.005			VA05083939	
1	1	0.4	0.4	65		2.0	k/s	5														B365497	217.93	219.46	0.078			VA05083939	1.53
1	2	1.8	1.8	70						5.0																			
0																						B365498	219.46	220.10	0.270			VA05083939	0.64
4	1	14.0	23.0	45	60					5.0												B365499	220.10	220.98	4.330			VA05083939	0.88
1	6	8.0	8.0	45						80.0																			
2	1	10.0	11.0	80	5					8.0												B365500	220.98	222.50	0.881			VA05083939	1.52
6	1	1.0	2.5	70						5.0												B365501	222.50	224.03	0.072			VA05083939	1.53
1	2	0.4	0.4	70																									
1	6	0.5	0.5	70						90.0																			
6	1	1.0	2.5	70						5.0												B365502	222.50	224.03	0.067	DUP		VA05083939	1.53
1	2	0.4	0.4	70																									
1	6	0.5	0.5	70						90.0																			
8	1	0.6	3.0	70		2.0	5	5		1.0	4.0											B365503	224.03	225.55	0.296			VA05083939	1.52
2	1	0.3	0.6	70							1.0											B365504	225.55	227.08	0.157			VA05083939	1.53
6	1	1.2	4.5	70	40						1.0											B365505	227.08	228.60	0.098			VA05083939	1.52
2	1	0.4	0.6	70							1.0											B365506	228.60	230.12	0.099			VA05083939	1.52
3	1	0.5	1.5	70							2.0											B365507	230.12	231.65	0.313			VA05083939	1.53
3	1	1.0	3.0	70							1.0											B365508	231.65	233.17	0.069			VA05083939	1.52
3	1	1.0	3.0	70							1.0											B365509	231.65	233.17	0.060	PD/CA		VA05083939	1.52
																						B365510	STANDARD 5E		1.435	5E		VA05083939	

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		251.71	258.52	GND: Fine grained Quartz-rich granitoid (GND?); Sericite altered; Irregular k-spar veinlets throughout; Quartz vein at 256.43m (50°) shows dextral displacement (0.4cm) along 60° fracture; Sharp up-hole contact adjacent to quartz veins at 55°; Down hole ctc is sharp and irregular, greyish-white quartz vein crosscuts ctc at 60°; Pyrite smearing on slip faces common; Slickenlines: @ 251.80m = 70°/80°; @ 252.6m = 25°/70°; @ 255.28m = 60°/70°; @ 256.1m = 20°/85°.		5				
10		258.52	271.27	GND: GND has been intensely altered with abundant k-spar (propylitic alt'n); Intervals of unaltered grey GND locally; From 260.09 - 260.47m core appears greyish-green and is very hard (possible silicification followed by sericite alt'n), similarly between 261.89 - 262.13m and 202.8 - 263.0m; Locally core is heavily fractured (263.0 - 263.45m) with carbonate and ser/chlorite on fracture faces; Slickenlines: @ 262.33m = 20°/10°; 263.70m = 50°/5° TCA.		5				4

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	0.8	2.1	70							1.0	0.1										B365511	233.17	234.87	**0.402**			VA05083939	1.70
1	1	0.4	0.4	50																		B365512	234.87	235.35	**0.383**			VA05083939	0.48
2	2	0.5	1.0	80																									
1	1	1.0	1.0	70							1.0											B365513	235.35	236.22	**0.716**			VA05083939	0.87
3	1	0.6	1.2	70							1.0	0.1			0.1							B365514	236.22	237.74	**0.075**			VA05083939	1.52
7	1	0.5	2.2	70							1.0	0.1										B365515	237.74	239.27	**0.133**			VA05083939	1.53
																						B365516	BLANK		**<0.005**			VA05083939	
5	1	1.5	4.3	70	40					1.0	2.0	0.1										B365517	239.27	239.90	**1.910**			VA05083939	0.63
1	2	2.0	2.0	45																									
2	1	0.5	0.7	70		0.3	s	3			2.0											B365518	239.90	240.94	**0.082**			VA05083939	1.04
5	1	0.6	2.0	70	80	1.0	s	3			2.0	0.1										B365519	240.94	242.32	**0.142**			VA05083939	1.38
1	6	0.3	0.3	60							50.0																		
2	1	1.0	2.0	70		2.0	s	5			1.0											B365520	242.32	243.84	**0.363**			VA05083939	1.52
2	1	0.5	0.9	70		0.6	s	5			5.0											B365521	243.84	244.88	**0.062**			VA05083939	1.04
2	1	0.5	0.9	70		0.6	s	5			5.0											B365522	243.84	244.88	**0.032**	DUP		VA05083939	1.04
1	1	1.5	1.5	45																		B365523	244.88	245.80	**0.174**			VA05083939	0.92
2	2	1.0	1.5	70						2.0																			
1	6	0.2	0.2	60						99.0																			
1	1	0.5	0.5	70																		B365524	245.80	246.89	**0.933**			VA05083939	1.09
4	2	0.5	1.2	70						5.0												B365525	246.89	248.11	**0.181**			VA05083939	1.22
1	6	0.2	0.2	80						80.0																			
3	1	0.5	0.5	70							3.0																		
3	1	3.0	6.5	45	70						1.0											B365526	248.11	249.49	**0.112**			VA05083939	1.38
6	2	0.5	3.0	80							0.1											B365527	249.49	251.71	**0.281**			VA05083939	2.22
1	6	1.0	1.0	70						40.0																			
6	1	0.7	2.8	60	45	1.0	s	5		2.0	2.0		0.1									B365528	251.71	252.98	**1.470**			VA05083939	1.27
6	1	0.7	2.8	60	45	1.0	s	5		2.0	2.0		0.1									B365529	251.71	252.98	**1.155**	PD/CA		VA05083939	1.27
																						B365530	STANDARD 7G		**4.470**	7G		VA05083939	
4	1	0.5	1.4	70	50	0.5	s	1		2.0	0.1											B365531	252.98	254.51	**0.297**			VA05083939	1.53
1	6	0.2	0.2	70						90.0																			
2	2	0.3	0.5	45	1	s	3		5																				
1	1	0.5	0.5	60						5.0												B365532	254.51	256.03	**0.207**			VA05083939	1.52
5	1	0.5	2.1	60		1.0	s/k	5		2.0												B365533	256.03	257.56	**0.131**			VA05083939	1.53
7	1	0.6	3.5	60						1.0												B365534	257.56	258.52	**0.128**			VA05083939	0.96
3	1	0.3	0.9	70	45	0.5	s	5		1.0												B365535	258.52	259.08	**0.390**			VA05083939	0.56
																						B365536	BLANK		**<0.005**			VA05083939	
5	1	1.0	5.5	45	70	0.6	s	5		1.0	1.0	0.1										B365537	259.08	260.60	**0.624**			VA05083939	1.52
1	3	0.4	0.4	30		0.4	s	5																					
2	1	0.4	0.7	70	60						1.0											B365538	260.60	262.13	**0.103**			VA05083939	1.53
2	2	0.4	0.8	70																									
2	1	0.4	0.8	60	70						2.0											B365539	262.13	263.00	**0.330**			VA05083939	0.87
1	6	0.4	0.4	60						15.0																			
1	3	1.0	1.0	60						5.0	10.0																		
0																						B365540	263.00	263.45	**0.143**			VA05083939	0.45
1	1	0.5	0.5	30																		B365541	263.45	264.53	**0.356**			VA05083939	1.08
1	1	0.5	0.5	30																		B365542	263.45	264.53	**0.255**	DUP		VA05083939	1.08
2	1	0.7	1.0	30						0.1												B365543	264.53	265.18	**0.198**			VA05083939	0.65
5	1	0.6	2.5	45	60					2.0												B365544	265.18	266.70	**0.639**			VA05083939	1.52
4	1	0.5	1.2	30	70					2.0	1.0		0.1		0.1							B365545	266.70	268.22	**3.410**			VA05083939	1.52
4	1	0.8	2.0	45	70	1.0	s	5			2.0											B365546	268.22	269.75	**0.212**			VA05083939	1.53
5	1	2.5	5.2	30	150					1.0	1.0											B365547	269.75	271.27	**0.103**			VA05083939	1.52

DRILL LOG LEGEND P1	DATE: September 2 - 5, 2005 PAGE 13 of 14		
DRILL HOLE # : DG05-306C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				EOH						

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 2 - 5, 2005

LOGGED BY: Kevin Piepgrass

PAGE 14 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL														Interval						
						Selvages				Sulphides								Oxidation				Sample Number								
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width (m)
4	2	0.4	1.0	60	80	2.5	s	5																						
																							EOH						

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-307C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1113m

BEARING: 000 | DIP: -50°

DATES DRILLING:	DATES LOGGING:
Aug 17 - 23, 2005	Sept 4 - 8, 2005

LOGGED BY:
Melodie Stone

CONTRACTOR:
Britton Brothers

COORD SYSTEM: NAD 27: EASTING: 459956 NORTHING: 7099141
COORD SYSTEM: NAD 83: EASTING: 459837 NORTHING: 7099322
NAD 27 (CORRECTED for historic grid): EASTING: 459926 NORTHING: 7099151
SECTION LINE(historic grid): 459925 E

DRILLING DETAILS

Hole Diameter: HQ
Overburden:
Deviation:
Casing: 28 ft (8.53m)
Core Size: HQ
Cement (# Bags): 0
Plug Depth: N/A
Notes: No plug necessary.

SAMPLING DETAILS

Sample Sequence: B364874 - B364925
Requisition #: MASP448STRGOL.05Q Date Shipped: 13-Sept-05
Lab Record #: VA05083121 Date Received: 28-Sept-05

Sample Sequence: B364926-B364925
Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05
Lab Record #: VA05082694 Date Received: 27-Sept-05

Sample Sequence: B365026 - B365127
Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05
Lab Record #: VA05082694 Date Received: 27-Sept-05

Duplicates:	364882; 364902; 364922; 364942; 364962; 364982; 365002; 365022; 365042; 365062; 365082; 365102; 365122
Preparation Duplicate/ Check Assay:	364889; 364909; 364929; 364949; 364969; 364989; 365009; 365029; 365049; 365069; 365089; 365109
Standards:	364890 (4D); 364910 (7G); 364930 (3C); 364950 (1A); 364970 (5E); 364990 (7G); 365010 (6F); 365030 (2B); 365050 (5E); 365070 (6F); 365090 (4D); 365110 (1A)
Blanks:	364876; 364896; 364916; 364936; 364956; 364976; 364996; 365016; 365036; 365056; 365076; 365096; 365116

FROM	TO	LITHOLOGY
6.71	291.08	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
30.48	335.3	-48.5	001.3	002.3
99.06	336.6	-46.8	002.6	003.6
190.49	336.5	-45.4	002.5	003.5
291.07	335.7	-44.0	001.7	002.7

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 1 of 14		
DRILL HOLE # : **DG05-307C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0.00 - 6.71	0.00	6.71	Casing						
10	6.71 - 291.08	6.71	38.10	GND: Pervasively moderately oxidized GND, such that overall colour is medium greyish brown; GND texture medium grained; Throughout section, there are ≥1cm quartz veins and grouped 0.5cm quartz veins with minimal mineralization, all oxidized or altered to biotite; Selvages are carb-quartz altered and small; @27m one 10cm zone of pervasive alteration includes sericite, silicification, muscovite and rusty oxidized hematite, 0.4cm in width, 3cm long.	3	0	0	1	2	
10		38.10	61.18	GND: GND even more oxidized, broken up to crumbly; Recovery moderate; Veins continue but are less visible due to amount of breakage; Veins contain greater concentration (up to 5%) of oxidized hematite and ~2% of massive metallic silver to tarnished black sulphide (chromite?), soft; @ 50.5m a 40cm zone of silicification and carbonitization (totally oxidized) surrounds 2 quartz veins and one carbonate veinlet. This same alteration forms wide selvages (~10cm, avg) around veinlets of carbonate and oxidized pyrite (? black, opaque), often breaking at veinlet; Larger quartz veins often have ~2% open space where it appears minerals have weathered away or 'popped' out during transport; @ 54.2m a zone of carbonate-rich oxidized clay/fault gouge appears, texture fine sand (<1mm).	4	0	0	1	3	
10		61.18	86.87	GND: Very crumbly section; Oxidation/limonite continues. 10% of section is in pieces <1cm, down to fine sand; Maximum length of competent core is 14cm, rarely full diameter; Unknown metallic silver/tarnished black sulphide seen here associated with sphalerite; could be galena but not supershiny metallic as mentioned above	4	1		2	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

	VEINS					Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
0																						B364874	6.71	7.62	**0.415**			VA05083121	0.91
5	1	2.0	4.5	40		2.0	q/cb	2	2	0.1			0.1					2.0				B364875	7.62	9.14	**0.084**			VA05083121	1.52
																						B364876	BLANK		**<0.005**			VA05083121	
4	1	1.0	4.0	60		4.0	q/cb	3	2	2.0								5.0				B364877	9.14	10.67	**0.729**			VA05083121	1.53
5	1	1.0	2.5	409		2.0	q/cb	2	2	1.0								5.0				B364878	10.67	12.19	**2.01**			VA05083121	1.52
3	1	1.5	3.0	50	35	4.0	q/cb	4	3								2.0					B364879	12.19	13.72	**0.378**			VA05083121	1.53
4	1	2.0	4.5	50		1.0	q/cb	4	4	1.0			0.1					5.0				B364880	13.72	15.24	**0.238**			VA05083121	1.52
6	1	3.0	7.0	30	45	2.0	q/cb	4	3	1.0								5.0				B364881	15.24	16.76	**2.21**			VA05083121	1.52
6	1	3.0	7.0	30	45	2.0	q/cb	4	3	1.0								5.0				B364882	15.24	16.76	**3.28**	DUP		VA05083121	1.52
2	1	1.0	2.0	50		8.0	cb/b	5	3						2.0							B364883	16.76	18.29	**0.033**			VA05083121	1.53
3	1	2.0	3.7	40		2.0	cb/q	4	2								0.1					B364884	18.29	19.81	**0.371**			VA05083121	1.52
4	1	1.5	4.0	50		1.0	q/cb	3	3	0.1								5.0				B364885	19.81	21.34	**0.338**			VA05083121	1.53
1	3	2.5	2.5	35		1.0	cb/q	2	3	1.0							2.0	5.0											
5	1	2.0	7.0	50		2.0	q/cb	3	4	2.0								5.0				B364886	21.34	22.86	**0.434**			VA05083121	1.52
5	1	1.0	4.5	40	20	1.0	q/cb	3	2	0.1								5.0				B364887	22.86	24.38	**3.42**			VA05083121	1.52
5	1	1.2	5.5	30	50	2.0	q/cb	3	3						1.0							B364888	24.38	25.71	**0.62**			VA05083121	1.33
5	1	1.2	5.5	30	50	2.0	q/cb	3	3						1.0							B364889	24.38	25.71	**0.76**	PD/CA		VA05083121	1.33
																						B364890	ANDARD 4D		**0.341**	4D		VA05083121	
6	1	1.0	4.0	60	35	1.0	q/cb	4	3	1.0					3.0			5.0				B364891	25.71	27.43	**0.624**			VA05083121	1.72
6	1	5.0	12.0	40		2.0	q/cb	3	3													B364892	27.43	28.96	**2.07**			VA05083121	1.53
6	1	3.0	8.0	60		2.0	q/cb	4	2	2.0								3.0				B364893	28.96	30.48	**0.165**		Broken core	VA05083121	1.52
3	1	1.0	3.0	60		3.0	q	3	3	1.0								3.0		1.0		B364894	30.48	32.00	**0.397**			VA05083121	1.52
0																						B364895	32.00	33.53	**0.657**			VA05083121	1.53
																						B364896	BLANK		**<0.005**			VA05083121	
3	1	1.5	3.5	50		1	q	2	2	1								5.0				B364897	33.53	35.05	**0.346**			VA05083121	1.52
3	1	1.0	3.0	50		3.0	q/cb	4	3													B364898	35.05	36.58	**0.069**			VA05083121	1.53
4	1	3.0	7.5	60		2.0	q/cb	4	4	0.1								5.0				B364899	36.58	38.10	**0.273**			VA05083121	1.52
6	1	1.0	5.0	30	60	8.0	q	4	4	1.0								5.0		3.0		B364900	38.10	39.62	**0.783**			VA05083121	1.52
3	1	1.5	3.5	45		2.0	q	3	3					1.0								B364901	39.62	41.15	**0.061**			VA05083121	1.53
3	1	1.5	3.5	45		2.0	q	3	3					1.0								B364902	39.62	41.15	**0.116**	DUP		VA05083121	1.53
4	1	2.0	8.0	45		2.0	q	3	4	0.1							3.0	5.0				B364903	41.15	42.67	**0.119**			VA05083121	1.52
0																						B364904	42.67	44.20	**0.218**			VA05083121	1.53
4	1	0.5	2.0	50		2.0	q/cb	4	4								1.0					B364905	44.20	45.72	**0.062**			VA05083121	1.52
5	1	2.0	5.2	45		2.0	q/cb	3	5	0.1							1.0	5.0				B364906	45.72	47.24	**0.803**			VA05083121	1.52
4	1	3.0	5.5	60		1.0	q/cb	3	5	0.1							1.0	5.0				B364907	47.24	48.77	**0.367**			VA05083121	1.53
3	1	2.0	4.0	65	4	q	4	2	0									5.0				B364908	48.77	50.29	**0.164**			VA05083121	1.52
3	1	2.0	4.0	65	4	q	4	2	0									5.0				B364909	48.77	50.29	**0.109**	PD/CA		VA05083121	1.52
																						B364910	ANDARD 7G		**4.42**	7G		VA05083121	
1	1	1.0	1.0	60		40.0	q/cb	5	5	0.1								5.0				B364911	50.29	51.82	**0.268**			VA05083121	1.53
1	4	0.2	0.2	50																							Same orange selvage		
3	1	1.0	3.0	45		2.0	q/cb	3	4	1.0								5.0				B364912	51.82	53.34	**0.593**			VA05083121	1.52
2	1	1.0	1.5	50		2.0	q/cb	2	4	1.0								5.0				B364913	53.34	54.86	**0.178**			VA05083121	1.52
2	1	1.0	2.0	60	45	1.0	q/cb	2	3	2.0								5.0				B364914	54.86	56.39	**0.076**			VA05083121	1.53
0																						B364915	56.39	57.91	**0.04**			VA05083121	1.52
																						B364916	BLANK		**0.683**			VA05083121	
5	1	3.0	7.0	40	60	3.0	q/cb	4	4						4.0		0.1					B364917	57.91	59.44	**0.469**			VA05083121	1.53
4	1	1.0	4.0	50		1.0	q/cb	5	4		5.0											B364918	59.44	60.21	**0.338**			VA05083121	0.77
3	1	1.5	4.0	40	60	6.0	q/cb	4	2		5.0		1.0									B364919	60.21	61.18	**0.073**			VA05083121	0.97
3	1	1.0	2.5	40		3.0	q/cb	3	4						5.0							B364920	61.18	62.48	**0.834**			VA05083121	1.30
1	1	1.0	1.0			1.0	q/cb	2	3													B364921	62.48	64.01	**0.197**			VA05083121	1.53
1	1	1.0	1.0			1.0	q/cb	2	3													B364922	62.48	64.01	**0.249**	DUP		VA05083121	1.53

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 3 of 14		
DRILL HOLE # : DG05-307C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		86.87	110.50	GND: Slightly more competent GND but oxidation still pervasive; Carb-rich selvages reduced to fine sand texture over <5% of section; First 2m of section show moderate alteration in selvages and are quite competent (90%); Strong slickensides in carbonate/limonite on fracture faces at 40° TCA; @ 92.96m, a 40cm zone of sericite alteration occurs, with sericite. Carb influx and a loss of GND texture. A 0.2cm veinlet of oxidized iron product (hematite) may account for some of this alteration - a channel for hydrothermal waters. No slickensides but ductile shear is a possiblity here; From 96.01 - 97.54m fractures at 0° TCA break up rock which appears previously silicified and coarse-grained (up to 1cm grains of quartz and masses of biotite). @100.58m, clear large quartz veins with >5% sphalerite begin. Core is more competent here as well, to 107.25m; @ 103.63m, disseminated aspy seen covering ~5% of fracture face, no associated vein seen.	3	1	0	1	2	
10		110.50	117.35	GND: Oxidation much less prevalent but mineralogically and texturally altered with sericite, carbonate and chlorite; Evidence of shear and faulting: @ 111.45m, a fracture plane at 15° TCA has 2 sets of slickensides at 90° to one another (conjugate), expressed in bt, ser, chl, carb, hem (ox'd); On one side of this fracture, quartz veins appear while on the other side are none (plane of motion); Mineralization concentrated at margins of quartz veins, sometimes appearing as separate sulphide veins (at slightly different angles, possibly a later generation of the quartz veins); One set of slickensides @ 112.70m on fracture face at 30° TCA; From 115.82 - 117.2m influx of carbonate weakens rock along irregular fractures.	1	1	1	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

Date: September 4 - 8, 2006

LOGGED BY: Melodie Stone

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Interval						
										Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scoordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
6	1	1.0	5.0	45		10.0	q/cb/s	5	4						1.0							B364923	64.01	65.53	**0.305**			VA05083121	1.52
2	3	0.2	0.4	55		1.0	q/cb	3	0		4.0																		
2	1	1.0	1.5	40	50	2.0	q/cb	4	4						5.0							B364924	65.53	67.06	**0.303**			VA05083121	1.53
2	1	0.5	1.0	50	0	2.0	q/cb	4	4						3.0							B364925	67.06	68.58	**0.044**			VA05083121	1.52
2	1	0.5	1.0			3.0	q	3	3						2.0							B364926	68.58	70.10	**0.058**			VA05082694	1.52
1	1	0.5	0.5	20		0.5	q	3	2													B364927	70.10	71.63	**0.065**			VA05082694	1.53
1	1	1.3	1.3	50		0.5	q/cb	4	1						0.1							B364928	71.63	73.15	**0.048**			VA05082694	1.52
1	1	1.3	1.3	50		0.5	q/cb	4	1						0.1							B364929	71.63	73.15	**0.062**	PD/CA		VA05082694	1.52
																						B364930	ANDARD 3C		**0.088**	3C		VA05082694	
1	1	1.0	1.0	50		8.0	cb	3	4										3.0	2.0		B364931	73.15	74.68	**0.131**			VA05082694	1.53
2	1	1.0	2.0	40		0.0			4	0.1								5.0				B364932	74.68	76.20	**0.133**			VA05082694	1.52
2	3	0.3	0.6	50	30	1.0	q/cb	3	1																				
2	1	2.0	3.0			4.0	q/cb	2	1	0.1								5.0				B364933	76.20	77.72	**0.176**		Pieces	VA05082694	1.52
8	1	1.0	5.5	50	130	1.0	q/cb	3	3						5.0		1.0	2.0				B364934	77.72	79.25	**0.229**			VA05082694	1.53
3	1	2.0	4.5	60		2.0	q/s	2	2	0.1					2.0			5.0				B364935	79.25	80.77	**0.269**			VA05082694	1.52
																						B364936	BLANK		**<0.005**			VA05082694	
4	1	1.5	4.0	60		2.0	q/cb/s	4	1								5.0					B364937	80.77	82.30	**0.13**			VA05082694	1.53
2	1	1.2	2.1	40		0.5	q/cb/s	3	2	0.1								5.0				B364938	82.30	83.82	**0.286**			VA05082694	1.52
2	1	1.0	2.0	30	50	0.0																B364939	83.82	85.34	**0.191**			VA05082694	1.52
2	1	1.5	2.0	50	70	2.0	q/s	2	3													B364940	85.34	86.87	**0.472**			VA05082694	1.53
4	1	2.0	4.2	30	50	2.0	q/cb/s	3	3						3.0							B364941	86.87	88.39	**0.114**			VA05082694	1.52
4	1	2.0	4.2	30	50	2.0	q/cb/s	3	3						3.0							B364942	86.87	88.39	**0.406**	DUP		VA05082694	1.52
3	1	1.0	2.4	45	0	8.0	q/s/cb	5	4	0.1								5.0				B364943	88.39	89.92	**1.245**			VA05082694	1.53
4	1	2.0	4.0	30	50	6.0	q	3	3	0.1					2.0			5.0				B364944	89.92	91.44	**0.054**			VA05082694	1.52
3	1	2.0	4.0	45	0	1.0	q/cb/s	3	3	0.1			0.1					4.0				B364945	91.44	92.96	**0.035**		Tiny fresh aspy	VA05082694	1.52
2	1	1.0	2.0	0		1.0	q	2	3													B364946	92.96	94.49	**0.065**			VA05082694	1.53
1	4	0.4	0.4	20		2.0	cb	3	2																				
3	1	1.5	3.0	30	40	1.0	q/cb/s	2	2													B364947	94.49	96.01	**0.212**			VA05082694	1.52
0																						B364948	96.01	97.54	**0.432**			VA05082694	1.53
0																						B364949	96.01	97.54	**0.551**	PD/CA		VA05082694	1.53
																						B364950	ANDARD 1A		**0.901**	1A		VA05082694	
2	3	1.0	2.0	40		1.0	cb/q	3	3				4.0						2.0	5.0		B364951	97.54	99.06	**0.493**			VA05082694	1.52
3	1	1.2	3.4	30	60	1.0	q/cb	3	3	1.0			2.0					5.0				B364952	99.06	100.58	**0.129**			VA05082694	1.52
3	1	2.0	4.0	45		2.0	q/cb	3	2	0.1			0.1		8.0							B364953	100.58	102.11	**0.555**			VA05082694	1.53
5	1	2.0	6.5	40	70	2.0	q/s/cb	3	4				1.0		5.0				2.0	3.0		B364954	102.11	103.63	**0.156**			VA05082694	1.52
4	1	2.0	5.0	60		10.0	q/cb	5	2				2.0		5.0					5.0		B364955	103.63	105.16	**0.507**			VA05082694	1.53
2	3	1.0	1.5	50	40	2.0	cb/q	3	3				0.1																
																						B364956	BLANK		**<0.005**			VA05082694	
3	1	1.5	3.5	55		1.5	q	3	2		2.0		0.1		1.0					1.0		B364957	105.16	106.68	**0.138**			VA05082694	1.52
3	1	1.0	1.6	45		1.0	q/cb	3	1		0.1				0.1					1.0		B364958	106.68	108.20	**0.34**			VA05082694	1.52
2	1	1.0	2.0	40		2.0	q	2	2						0.1							B364959	108.20	109.73	**0.092**			VA05082694	1.53
1	6	0.4	0.4	65		2.0	q/cb	4	2						10.0				40.0										
4	1	1.5	4.0	50		2.0	q/s/cb	3	3		0.1				0.1							B364960	109.73	110.50	**0.388**			VA05082694	0.77
6	1	1.0	4.5	50	35	18.0	s/chl	4	2	10.0	0.1		0.1		0.1							B364961	110.50	111.25	**0.466**			VA05082694	0.75
6	1	1.0	4.5	50	35	18.0	s/chl	4	2	10.0	0.1		0.1		0.1							B364962	110.50	111.25	**0.379**	DUP		VA05082694	0.75
5	1	2.0	6.0	50	35	20.0	s/cb/chl	5	2	10.0	2.0		10.0									B364963	111.25	112.03	**0.472**			VA05082694	0.78
5	1	2.0	5.0	50	25	2.0	q/cb	4	1		10.0		2.0		5.0				2.0			B364964	112.03	112.78	**0.324**			VA05082694	0.75
7	1	2.5	6.7	50		4.0	q/cb	3	2		5.0	0.1	1.0		0.1				2.0			B364965	112.78	114.30	**0.092**			VA05082694	1.52
4	3	1.5	4.0	50		2	q/cb/s	4	1				6.0																
5	1	2.5	6.0	25	50	2.0	q/cb	4	1		10.0	2.0	1.0									B364966	114.30	115.82	**0.133**			VA05082694	1.52

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 5 of 14		
DRILL HOLE # : DG05-307C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.35	128.02	GND: Unaltered GND with mineralized, frequent quartz veins; Sphalerite continues, as well as massive po with a relatively large amount of cpy. Aspy appears irregularly (locally up to 10%, and association with quartz vein - may be later); Large vein @ 119.90m contains well-formed, shiny large biotite within vein.	1	1	1	0	1	
10		128.02	134.11	GND: Increase in carbonate with limonite along 30° and 130° fract, plus at irregular angles; Weakens and breaks rocks into <1cm pieces in 3 zones; Longest competent core is 15cm; 75% unaltered GND - alteration occurs in small selvages surrounding quartz veins, carbonate veinlets and the last sample of the interval is gradation into sericite-rich zone.	2	2	0	1	2	
10		134.11	138.27	GND: Zone of extreme alteration: sericitized, predominantly, plus moderate carbonitization; Only quartz eyes left of GND texture and overall colour is dark bluish green; Limonite on most fracture faces with some infiltration (selvages up to 1cm) into surrounding rock; 'Veins' noted are not solid or straight - only chunks of quartz in a line: chunks are rounded and have sulphides (partially oxidized py) within interstices of quartz.	2	5	2	0	2	
10		138.27	142.71	GND: Still highly altered, but with more carbonate, in anhedral to subhedral laths up to 3cm long and 0.5cm wide, within lighter blue-green matrix than previous section.	1	5	1	1	3	
10		142.71	147.83	GND: Approx 50% unaltered, unoxidized GND; Wide (10cm) oxidation selvages around cracks/veinlets of limonite; Quartz veins and sulphide veins have selvages as well, and irregular veinlets of limonite continue through section; Massive pyrite associated with >2cm quartz veins is linearly distributed through vein as well as 10cm of vein, in same orientation.	2	2	0	0	2	
10		147.83	153.16	GND: Wide selvages around qtz and sulphide veins dominate section; Med grained unaltered GND.	1	3	0	0	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2006

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL															Interval						
						Selvages				Sulphides										Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
2	1	1.0	2.0	20	50	2.0	q/s/cb	2	0		2.0								3.0			B364967	115.82	117.35	**0.103**			VA05082694	1.53
8	1	1.0	8.0	50	40	1.0	q/cb	3	1		5.0	1.0	1.0		2.0							B364968	117.35	118.87	**0.367**			VA05082694	1.52
8	1	1.0	8.0	50	40	1.0	q/cb	3	1		5.0	1.0	1.0		2.0							B364969	117.35	118.87	**0.101**	PD/CA		VA05082694	1.52
																						B364970	ANDARD 5E		**1.385**	5E		VA05082694	
5	1	1.5	4.5	50	65	4.0	q	3	1		2.0								2.0			B364971	118.87	120.40	**0.044**			VA05082694	1.53
3	1	6.0	8.0	45		3.0	q/s/cb	3	1		8.0	1.0	5.0		2.0				3.0	10.0		B364972	120.40	120.98	**0.216**			VA05082694	0.58
1	3	0.4	0.4	45		1.0	q/cb	4	0		0.1																		
5	1	15.0	18.0	40	50	0.5	q/s/cb	2	0	1.0	5.0		2.0		6.0				1.0			B364973	120.98	121.92	**5.99**			VA05082694	0.94
4	1	3.0	7.0	45		2.0	q/s/cb	4	0		6.0		4.0						1.0	1.0		B364974	121.92	123.44	**0.327**			VA05082694	1.52
9	1	2.0	9.0	40	50	2.0	q/cb	2	0		8.0		2.0									B364975	123.44	124.97	**0.112**			VA05082694	1.53
																						B364976	BLANK		**<0.005**			VA05082694	
6	1	1.5	5.5	40	50	2.0	q	0		3.0										4.0		B364977	124.97	126.49	**0.313**			VA05082694	1.52
3	1	1.0	3.0	30		1.0	q	3	0		3.0									1.0		B364978	126.49	128.02	**0.063**			VA05082694	1.53
4	1	0.5	2.0	50		1.0	q/cb	3	0		2.0		0.1						1.0	1.0		B364979	128.02	129.54	**0.211**			VA05082694	1.52
5	1	0.5	2.5	50		1.0	q	2	2		4.0		0.1						2.0			B364980	129.54	131.06	**0.222**			VA05082694	1.52
2	1	1.5	2.0												0.1							B364981	131.06	132.59	**0.658**		Broken core	VA05082694	1.53
2	1	1.5	2.0												0.1							B364982	131.06	132.59	**0.781**	DUP		VA05082694	1.53
2	1	3.0	4.0	40		0.5	q/cb	3	1	2.0			0.1					4.0				B364983	132.59	134.11	**0.23**			VA05082694	1.52
1	1	4.0	4.0	30		0.0				10.0								1.0				B364984	134.11	135.64	**0.274**			VA05082694	1.53
2	1	1.0	2.0	10		0.0				2.0												B364985	135.64	137.16	**0.058**			VA05082694	1.52
3	1	1.0	3.0	30		0.0				2.0												B364986	137.16	138.27	**0.346**			VA05082694	1.11
1	6	4.0	4.0	40						100.0								5.0				B364987	138.27	139.16	**0.34**		All alt'd, all py ox'd	VA05082694	0.89
5	1	5.0	9.0	60	110					1.0												B364988	139.16	140.21	**0.094**			VA05082694	1.05
5	1	5.0	9.0	60	110					1.0												B364989	139.16	140.21	**0.106**	PD/CA		VA05082694	1.05
																						B364990	ANDARD 7G		**4.54**	7G		VA05082694	
5	1	1.0	5.0	40	20					5.0								2.0				B364991	140.21	141.73	**0.133**			VA05082694	1.52
1	6	10.0	10.0	60						100.0								4.0											
0																						B364992	141.73	142.71	**0.059**			VA05082694	0.98
0																						B364993	142.71	143.26	**0.047**			VA05082694	0.55
8	1	1.0	8.0	60		2.0	q/s/cb	5	3	1.0	6.0		2.0		1.0			4.0				B364994	143.26	144.78	**0.561**			VA05082694	1.52
4	1	1.5	4.0	70		8.0	s/cb	4	3	4.0			2.0									B364995	144.78	146.30	**0.492**			VA05082694	1.52
1	6	2.0	2.0	70		30.0	s/cb	5	1	95.0								2.0											
																						B364996	BLANK		**<0.005**			VA05082694	
7	1	1.0	2.8	60		4.0	q/s	4	1	10.0	3.0							1.0				B364997	146.30	147.83	**0.366**			VA05082694	1.53
2	1	3.0	5.0	50		30.0	s	4	1	12.0	2.0		0.1									B364998	147.83	149.35	**0.149**		Massive py	VA05082694	1.52
4	1	1.0	4.0	50		4.0	5	4	1	10.0	5.0		0.1									B364999	149.35	150.03	**0.292**			VA05082694	0.68
2	6	1.0	2.0	60		20.0	cb/s	5		70.0																			
3	1	1.0	2.5	60																		B365000	150.03	150.88	**0.134**		Selvage not distinct from alt'n	VA05082694	0.85
1	4	0.3	0.3	40		15	cb/s	5	2	20								4.0											
2	1	2.0	3.0	50	130	10.0	s	5		5.0	0.1							2.0				B365001	150.88	151.64	**1.98**			VA05082694	0.76
2	6	4.0	4.0	130		30.0	s/cb	5	1	60.0								1.0											
2	1	2.0	3.0	50	130	10.0	s	5		5.0	0.1							2.0				B365002	150.88	151.64	**1.32**	DUP		VA05082694	0.76
2	6	4.0	4.0	130		30.0	s/cb	5	1	60.0								1.0											
4	1	1.0	3.0	45	60	15.0	s/q	5	0	3.0	2.0		2.0					1.0				B365003	151.64	152.40	**0.062**			VA05082694	0.76
1	3	0.3	0.3	30		2.0	q/cb/k	4	1		0.1									3.0									
6	1	2.0	6.0	50	60	2.0	s/cb/q	3	1		4.0		2.0									B365004	152.40	153.16	**0.363**			VA05082694	0.76
2	3	0.3	0.6	70		6.0	cb/s	5		30.0	6.0							3.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 1 of 14	
DRILL HOLE # : DG05-307C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		153.16	161.54	GND: Moderately to highly altered GND, surrounding numerous quartz and sulphide veins; Slickensides (weak to moderate) are seen throughout section, expressed in sericite + carbonate. Also motion along fractures-quartz veins truncated, and irregular in width and orientation; Because alteration is so pervasive in some areas (on 1-2m scale), selvage widths are difficult to distinguish, especially where veins are numerous; Pyrite in veins is predominantly fresh (not oxidized), but when associated with carbonate it is virtually all oxidized and clay rich; Regular fracturing @ 30 - 60° (variable across section, ~8 per m, straight).	1	4	1	1	3	
10		161.54	182.04	GND: Poor recovery. Rock is soft (sericite and carbonate altered) and is very broken up from 161.54 - 168.8m. Followed by very hard, silicified GND with little to no carbonate alteration, from 169.0 - 170.35m; Sericite still affecting this section, appears previous to silicification; Rock grades between two extremes (varying amounts of late carbonate) for whole section; Pyrrhotite appears 'fused' (black magnetic mass with the occasional fresh po within).	0	3	0	1	1	
10		182.04	183.44	GND: Weak, quartz-rich section of GND; Weakened by intense sericitization and carbonatization; Low specific gravity; Colour is white.		4		2	4	
10		183.44	213.60	GND: Moderately carb-altered God with sericitized selvages around medium to large (2-3cm) quartz veins (~2 per m) with mineralization; @ 192.5m, a 5cm zone with sharp boundaries at 15° TCA, appears to be sheared into position. These clues continue to end of section.	0	3	1	1	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
8	1	1.0	6.0	60			s/cb	4		5.0	1.0		0.1					4.0				B365005	153.16	153.92	**0.339**			VA05082694	0.76
2	1	3.0	4.0	75						5.0								4.0				B365006	153.92	154.72	**0.532**			VA05082694	0.80
2	6	1.0	2.0	75		4.0	cb/s	5	1	100.0								4.0											
6	1	1.0	6.0	70	50	2.0	q/s	3	0		8.0	0.1										B365007	154.72	155.45	**0.368**			VA05082694	0.73
6	1	2.0	6.0	50		2.0	q	3	1	0.1	3.0							5.0				B365008	155.45	156.97	**0.123**			VA05082694	1.52
6	1	2.0	6.0	50		2.0	q	3	1	0.1	3.0							5.0				B365009	155.45	156.97	**0.126**	PD/CA		VA05082694	1.52
																						B365010	ANDARD 6F		**2.91**	6F		VA05082694	
5	1	1.5	3.5	50		1.0	q	3	0	0.0		3.0										B365011	156.97	158.50	**0.067**			VA05082694	1.53
8	1	2.0	9.5	50		2.0	q/s/cb	3	1	1.0	5.0		0.1									B365012	158.50	160.02	**0.257**			VA05082694	1.52
5	1	2.0	5.0	70	40	4.0	q/cb/s	4			5.0									1.0		B365013	160.02	160.71	**0.833**		Py all oxidized	VA05082694	0.69
1	6	1.0	1.0	60		20.0	s	4		60.0								5.0											
4	1	2.0	7.0	30	75					2.0	5.0		0.1					4.0				B365014	160.71	161.54	**0.041**		All altered	VA05082694	0.83
1	1	11.0	11.0	60	150	70.0	cb	3	0	4.0								5.0				B365015	161.54	163.02	**0.626**			VA05082694	1.48
																						B365016	BLANK		**<0.005**			VA05082694	
2	1	1.0	1.5	50		1.0	q	3	0	1.0	4.0							3.0				B365017	163.02	164.59	**0.22**			VA05082694	1.57
4	1	1.0	4.0	60		0.0				0.1					0.1							B365018	164.59	166.12	**0.445**		Trace Sphalerite?	VA05082694	1.53
1	3	1.0	1.0	60		1.0	q	2											0.1			B365019	166.12	167.64	**0.033**			VA05082694	1.52
4	1	1.0	4.0	50		2.0	q/cb	2														B365020	167.64	169.16	**0.11**		Sulph clay	VA05082694	1.52
1	6	8.0	8.0	70			cb	3										100.0											
5	1	1.0	4.5	40		1.0	q	2														B365021	169.16	170.69	**0.054**			VA05082694	1.53
5	1	1.0	4.5	40		1.0	q	2														B365022	169.16	170.69	**0.792**	DUP		VA05082694	1.53
1	1	1.0	1.0			1.0	q	3										0.1				B365023	170.69	172.21	**0.027**		Very broken	VA05082694	1.52
1	1	1.5	1.5	70		1.0	q	2			3.0										2.0	B365024	172.21	173.74	**0.031**		Oxidized po?	VA05082694	1.53
2	3	0.3	0.6	60		2.0	q/s	3			5.0										1.0	B365025	173.74	175.26	**0.036**			VA05082694	1.52
3	1	2.0	4.0	40		4.0	q/s	3			10.0	2.0										B365026	175.26	176.78	**0.026**			VA05082695	1.52
5	1	4.0	8.5	20	40	1.0	q	2			2.0											B365027	176.78	178.31	**0.117**			VA05082695	1.53
2	1	1.0	2.0	50		1.0	q	2			5.0									1.0	2.0	B365028	178.31	179.83	**0.03**			VA05082695	1.52
2	1	1.0	2.0	50		1.0	q	2			5.0									1.0	2.0	B365029	178.31	179.83	**0.042**	PD/CA		VA05082695	1.52
																						B365030	ANDARD 2B		**3.06**	2B		VA05082695	
5	1	1.0	5.0	50		1.0	q	2			3.0									1.0		B365031	179.83	181.36	**0.057**			VA05082695	1.53
2	1	1.0	2.0	30		4.0	q/s	4												0.1		B365032	181.36	182.04	**0.067**			VA05082695	0.68
																						B365033	182.04	182.88	**0.513**			VA05082695	0.84
																						B365034	182.88	183.44	**0.046**			VA05082695	0.56
2	1	1.0	2.0	40		2.0	q/s	3	1		2.0										1.0	B365035	183.44	184.40	**0.106**			VA05082695	0.96
2	6	0.5	1.5	25		1.0	cb	5		6.0											2.0								
																						B365036	BLANK		**<0.005**			VA05082695	
5	1	1.0	4.5	60	40	3.0	q/s	4	0		1.0									4.0		B365037	184.40	185.93	**1.065**			VA05082695	1.53
5	1	2.0	4.0	50		1.0	q/s	4			6.0											B365038	185.93	187.45	**0.133**			VA05082695	1.52
4	1	10.0	15.5			15	s/chl	4	0	3.0		1.0										B365039	187.45	188.98	**0.526**			VA05082695	1.53
2	1	8.0	11.0	10		1.0	q/cb	2	0		2.0											B365040	188.98	190.50	**0.132**			VA05082695	1.52
2	1	3.0	4.0	35		2.0	q/3	3														B365041	190.50	192.02	**0.037**			VA05082695	1.52
1	6	0.5	0.8	35		10.0	cb	2										100.0											
2	1	3.0	4.0	35		2.0	q/3	3														B365042	190.50	192.02	**0.121**	DUP		VA05082695	1.52
1	6	0.5	0.8	35		10.0	cb	2										100.0											
2	1	1.0	2.0	50		6.0	q/s	3		3.0								1.0				B365043	192.02	193.50	**0.11**		Black clay beside quartz vein (carb-rich)	VA05082695	1.48
1	3	5.0	5.0	15		0.0																							
5	1	1.0	4.5	50	30	8.0	q/s	5			8.0							2.0				B365044	193.50	195.07	**0.166**			VA05082695	1.57
5	1	1.3	5.8	40		6.0	q/s	3			4.0							1.0				B365045	195.07	196.60	**0.343**			VA05082695	1.53
4	1	2.0	5.5	10		1.0	q	2			5.0									5.0		B365046	196.60	198.12	**0.076**			VA05082695	1.52
6	1	2.0	5.5	30	60	1.0	q	3		0.1	0.1							2.0				B365047	198.12	199.64	**0.064**			VA05082695	1.52
2	1	1.0	2.0	45		4.0	q/s	2			4.0											B365048	199.64	201.17	**0.39**			VA05082695	1.53
1	6	0.4	0.4	40		30.0	5	4		80.0								10.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005	PAGE 9 of 14	
DRILL HOLE # : **DG05-307C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		213.51	217.00	GND: Limonite appears again on fracture faces; GND competent with regular fracturing at 60° TCA.	1	1	0	0	1	
10		217.00	217.93	GND: Highly altered section; GND texture reduced to quartz eyes within sericitized/carbonate altered matrix; 2 to 3 quartz veins still visible with no distinguishable selvages; One quartz vein has ~60% oxidized pyrite, clay rich.	1	4	1	2	2	
10		217.93	225.55	GND with numerous medium-sized quartz veins; Late carbonate alteration moderate; Weak, broken up to crumbly rock.	0	2	0	1	3	
10		225.55	245.36	GND: Weak, crumbly carbonate-rich GND: Other than late carbonate, GND is unaltered except from 230.4 - 230.55m with a wide selvage around carb/oxidized pyrite clay vein-sericitized; Slickensides expressed in sericite and carbonate on fracture face @ 50° TCA; Sericite/carbonate for 10cm @ 241.4m surrounding quartz/carb vein; Increased sulphide content in veins is associated with larger selvages especially (oxidized) pyrite.	0	1	0	1	3	
10		245.36	254.51	GND: Competent core except in a few sericite-altered zones, from 246 - 246.7 (surrounding sulphide-rich quartz veins) and from 247.0 - 247.4m (same) and 247.8 - 248.0m, and 250.5 - 250.6m; These sericite zones are more crumbly than unaltered GND in between; Quartz veins toward the end of the section show decreased mineralization; The last 50cm is gradational to the next section.	0	2	0	0	1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

PAGE 10 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, ec = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL																				
						Selvages				Sulphides										Oxidation					Interval					
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
2	1	1.0	2.0	45		4.0	q/s	2			4.0											B365049	199.64	201.17	**0.327**	PD/CA		VA05082695	1.53
1	6	0.4	0.4	40		30.0	5	4		80.0								10.0												
																						B365050	ANDARD 5E		**1.44**	5E		VA05082695	
1	1	1.0	1.0	50		10.0	s/cb	4			10.0	1.0							6.0			B365051	201.17	202.69	**0.099**			VA05082695	1.52
4	1	2.0	5.5	50		2.0	q/s	2		0.1	0.1											B365052	202.69	204.22	**0.172**			VA05082695	1.53
6	1	2.0	6.5	30	70	2.0	s/q	3			2.0								3.0			B365053	204.22	205.74	**0.102**			VA05082695	1.52
1	1	1.5	1.5	25	165	2.0	q/s	2			4.0							1.0				B365054	205.74	207.26	**0.615**			VA05082695	1.52
5	1	2.0	5.5	50	30	8.0	s	4			6.0							2.0				B365055	207.26	208.79	**0.053**			VA05082695	1.53
																						B365056	BLANK		**<0.005**			VA05082695	
3	1	1.0	3.3	3	55	0.5	q	2			2.0											B365057	208.79	210.31	**0.088**			VA05082695	1.52
5	1	1.5	5.5	60	30	1.0	q	3			1.0							1.0				B365058	210.31	211.84	**0.41**			VA05082695	1.53
2	1	0.4	0.8	60		2.0	q/s	3			1.0							1.0				B365059	211.84	212.59	**0.042**			VA05082695	0.75
2	1	1.0	2.0	40		1.0	q	3			1.0							1.0				B365060	212.59	213.51	**0.078**			VA05082695	0.92
1	1	1.0	1.0	45		1.0	q/s	3			2.0								4.0			B365061	213.51	214.88	**0.117**			VA05082695	1.37
1	1	1.0	1.0	45		1.0	q/s	3			2.0								4.0			B365062	213.51	214.88	**0.056**	DUP		VA05082695	1.37
4	1	1.0	4.0	50		4.0	q/s	3			2.0									2.0		B365063	214.88	216.41	**0.085**			VA05082695	1.53
3	1	1.0	3.0	40		4.0	q/cb/s	4			0.1								2.0	2.0		B365064	216.41	216.81	**0.461**			VA05082695	0.40
2	1	1.0	2.0	40		6.0	q/s	3												0.1		B365065	216.81	217.93	**0.124**			VA05082695	1.12
1	6	1.0	1.0	70			s	5										60.0												
3	1	1.0	3.0	60		2.0	q/s	4			1.0									2.0		B365066	217.93	219.46	**0.042**		Oxidized py clay	VA05082695	1.53
3	1	1.0	3.0	65		2.0	q/s	2			3.0									1.0		B365067	219.46	220.98	**0.06**			VA05082695	1.52
4	1	1.0	4.0	45		2.0	q/cb/s	4			1.0										1.0	B365068	220.98	222.50	**0.152**			VA05082695	1.52
4	1	1.0	4.0	45		2.0	q/cb/s	4			1.0										1.0	B365069	220.98	222.50	**0.13**	PD/CA		VA05082695	1.52
																						B365070	ANDARD 6F		**2.94**	6F		VA05082695	
4	1	1.3	4.0	60	30	2.0	q/cb	3			5.0								1.0	2.0		B365071	222.50	224.03	**0.43**			VA05082695	1.53
5	1	1.5	5.5	50	10	2.0	q/cb	5			6.0	0.1						2.0		2.0		B365072	224.03	225.55	**0.488**			VA05082695	1.52
3	1	1.0	2.5	60		2.0	q/s	3			1.0							1.0				B365073	225.55	227.08	**0.298**			VA05082695	1.53
4	1	1.0	4.0	60		1.0	q/cb	2			4.0									2.0		B365074	227.08	228.60	**0.074**			VA05082695	1.52
3	1	1.0	3.0	50	30	1.0	q/cb	4			7.0							1.0		2.0		B365075	228.60	231.12	**1.13**			VA05082695	2.52
2	3	1.5	2.0	45		2.0	q	2			0.1								1.0											
																						B365076	BLANK		**<0.005**			VA05082695	
2	1	2.0	3.0	40	70	2.0	q/s	2			2.0									1.0		B365077	230.12	231.65	**0.148**			VA05082695	1.53
1	4	1.0	1.0	70		25.0	cb/s	5										40.0												
5	1	1.2	4.5	45		1.0	q/cb	4			3.0									2.0		B365078	231.65	233.17	**0.661**			VA05082695	1.52
4	1	1.5	4.0	60		2.0	q/cb/s	4			5.0										4.0	B365079	233.17	234.70	**1.575**			VA05082695	1.53
3	1	1.4	3.4	20	50	2.0	q/s	3			5.0											B365080	234.70	236.22	**0.091**			VA05082695	1.52
2	3	0.5	0.8	40		10.0	cb/s	4										10.0												
4	1	1.0	4.0	60		1.0	q/s	3			0.1								5.0	2.0		B365081	236.22	237.74	**0.704**			VA05082695	1.52
4	1	1.0	4.0	60		1.0	q/s	3			0.1								5.0	2.0		B365082	236.22	237.74	**0.694**	DUP		VA05082695	1.52
3	1	0.8	2.4			1.0	q/s	1	0		1.0											B365083	237.74	239.87	**0.053**			VA05082695	2.13
5	1	1.0	4.0	50	60	3.0	q/s	3		0.1	2.0								2.0			B365084	239.87	240.79	**0.082**			VA05082695	0.92
5	1	1.2	6.0	40		1.0	q	1			0.1									2.0		B365085	240.79	242.32	**0.213**			VA05082695	1.53
1	3	1.2	1.2	80		10.0	s/cb	4																						
4	1	1.0	4.0	60	40	2.0	q/s	2			1.0								5.0	0.1		B365086	242.32	243.84	**0.028**			VA05082695	1.52
4	1	1.0	4.0	55		1.0	q	4			2.0											B365087	243.84	245.36	**0.049**			VA05082695	1.52
5	1	1.0	4.5	60		30.0	s/cb	4		6.0	3.0							1.0		3.0	1.0	B365088	245.36	246.89	**0.368**			VA05082695	1.53
5	1	1.0	4.5	60		30.0	s/cb	4		6.0	3.0							1.0		3.0	1.0	B365089	245.36	246.89	**0.648**	PD/CA		VA05082695	1.53
																						B365090	ANDARD 4D		**0.447**	4D		VA05082695	
2	1	4.0	4.5	70		6.0	s/cb	5	2	5.0	10.0							10.0				B365091	246.89	248.41	**0.146**			VA05082695	1.52
1	6	0.5	0.5	60		50.0	s/chl	4	0	5.0								65.0												
4	1	1.0	3.0	35	55	2.0	q	3			1.0											B365092	248.41	249.94	**0.046**			VA05082695	1.53
3	1	0.8	1.5	70		1.0	q/cb	2			1.0							1.0				B365093	249.94	251.46	**0.077**			VA05082695	1.52
6	1	1.0	4.0	65		2.0	q/s	2			1.0							1.0				B365094	251.46	252.98	**0.109**			VA05082695	1.52
5	1	2.0	4.5	50		2.0	q/s	2		0.1	0.1											B365095	252.98	254.51	**0.076**			VA05082695	1.53
																						B365096	BLANK		**<0.005**			VA05082695	

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005 PAGE 11 of 14		
DRILL HOLE # : DG05-307C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		254.51	263.65	GND: Pervasively sericitized GND; Crumbly and clay-rich. Also carbonate-rich; Quartz eyes remain; Shear evidence in 'smeared' oxidized pyrite veinlets and quartz veins moved 1-2cm dextrally at 50° TCA; Selvages removed/not visible in altered matrix; Quartz veins only partial within altered matrix, often been sheared away; Carbonate veinlets and sulphide veins at 70-80° TCA.	1	5	0	3	3	
10		263.65	284.29	GND: Carbonate and sericite alteration still strong, but separated by medium to dark grey unaltered GND; Carbonate alteration more effective here, even unaltered GND is infused with it for 1-2m in bottom half of section (late carb); Colour of altered zones is more pale beige (early) than the blue-green of the last section (early = competent, late = crumbly); Section is 80% competent rock; Section is 10% unaltered GND to 277.37 and then 40% unaltered from 277.37 284.29m; Late carbonate effects both altered and unaltered GND trhoughout section; Alteration is not always attrubuted to veining, often no vein visible whre pervasive sericite/carbonate alteration appears; Slickensides visible on most fracture faces at 45° TCA; 'Bleached' section from 283.0m to 284.1m where color is yellowish white, contacts unaltered GND (upper) at 20° TCA; May be considered selvage around low-angle quartz veins and one high angle sulphide vein. Silicified.	1	4	1	2	4	
10		284.29	286.51	GND: Competent core; Unaltered with quartz veins to 285.5m, where fracture at 0-5° TCA (parallel for 1m) denotes shear zone boundary; Half of core is still unaltered with quartz veins (altered selvages) while half is totally carbonate and sericite infused and texture sheared through with carbonate and oxidized sulphide clays.	0	2	1	1	3	
10		286.51	288.39	GND: Sheared material now makes up entire core, apparent shear direction is @ 50° TCA; 70% of section is soft, clay-rich crumbly, carb-rich, sericitic gravel (quartz eyes) to clay texture. Veins seen in competent bits (pieces no longer than ~12cm). Contact with competent next section is at 55° TCA.	1	4	1	3	4	
10		288.39	291.08	GND: Unaltered GND between selvages surrounding quartz and carbonate veins with minimal mineralization.	0	2	0	0	3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides									Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	0.5	2.0	70	50					0.1								4.0				B365097	254.51	256.03	**0.14**		All Altered	VA05082695	1.52
2	1	1.0	1.5	50						0.1								1.0				B365098	256.03	257.56	**0.594**			VA05082695	1.53
2	1	1.0	1.6	50	30	0.0				0.1								3.0				B365099	257.56	259.08	**0.024**			VA05082695	1.52
3	1	0.5	1.5	30	80					8.0								2.0				B365100	259.08	260.60	**0.469**			VA05082695	1.52
3	6	2.0	5.0	70						70.0								30.0											
4	1	1.2	3.5	60	80	1.6	cb/s	5										5.0				B365101	260.60	262.13	**0.017**			VA05082695	1.53
2	4	0.5	1.0	80	110																								
4	1	1.2	3.5	60	80	1.6	cb/s	5										5.0				B365102	260.60	262.13	**0.019**	DUP		VA05082695	1.53
2	4	0.5	1.0	80	110																								
4	1	0.5	2.0	60	20					8.0								10.0				B365103	262.13	263.65	**0.24**			VA05082695	1.52
1	3	1.0	1.0	50														10.0											
3	6	2.0	4.5	60	140					70.0								30.0											
4	1	2.0	5.0	40	60	2.0	s/q	3		0.1	3.0							1.0				B365104	263.65	265.18	**0.057**			VA05082695	1.53
1	6	0.3	0.3	60		6.0	s/cb	4										90.0											
3	1	1.2	4.4	70		10.0	q/cb	4			0.1							2.0				B365105	265.18	266.70	**0.068**			VA05082695	1.52
7	1	1.0	4.5	65	40	10.0	cb/s	4			3.0							0.1				B365106	266.70	268.22	**0.151**			VA05082695	1.52
1	1	0.4	0.4	55		1.0	cb/s	4										0.1				B365107	268.22	269.75	**0.236**			VA05082695	1.53
2	6	0.4	0.8	45		6.0	cb/s	5		40.0								40.0											
5	1	1.0	3.6	60	70	1.0	cb	5		5.0								0.1				B365108	269.75	271.27	**0.184**		5% py in one vein only	VA05082695	1.52
2	3	4.0	5.0	60	70	20.0												10.0											
5	1	1.0	3.6	60	70	1.0	cb	5		5.0								0.1				B365109	269.75	271.27	**0.197**	PD/CA		VA05082695	1.52
2	3	4.0	5.0	60	70	20.0												10.0											
																						B365110	ANDARD 1A		**0.848**	1A	Po and py in different veins	VA05082695	
4	1	0.5	2.0	60		4.0	q/cb	4		4.0	7.0							2.0				B365111	271.27	272.80	**0.695**			VA05082695	1.53
1	1	1.0	1.0	60		0.5	cb	5		3.0								0.1				B365112	272.80	274.32	**0.037**			VA05082695	1.52
4	1	1.0	2.4	35		1.0	cb	4										0.1				B365113	274.32	275.84	**0.118**			VA05082695	1.52
3	3	1.0	2.2	30	70					5.0								1.0											
2	6	1.0	2.0	60		2.0	q/cb	4		30.0								40.0											
8	1	1.0	6.0	70	50	1.0	cb	4										2.0				B365114	275.84	277.34	**0.066**			VA05082695	1.50
2	3	1.5	2.9	115														10.0											
2	6	0.3	0.6	130						10.0								50.0											
9	1	1.0	6.5	40	70	2.0	q/cb	4		5.0								5.0				B365115	277.34	278.89	**0.31**			VA05082695	1.55
1	4	0.5	0.5	70		10.0	cb/s	4																					
																						B365116	BLANK		**<0.005**			VA05082695	
3	1	1.0	3.0	70	50	2.0	cb/q	4			1.0							5.0				B365117	278.89	280.42	**0.653**			VA05082695	1.53
1	6	0.4	0.4	140		10.0	cb/s	5	1	5.0								80.0											
5	1	1.0	4.0	40	60	2.0	q/cb	4			2.0							4.0				B365118	280.42	281.94	**0.143**			VA05082695	1.52
4	1	1.0	2.0	20		1.0	q/cb	4										2.0				B365119	281.94	283.46	**0.734**			VA05082695	1.52
2	6	0.2	0.4	30	40	20.0	cb/s	4		20.0								60.0											
2	1	1.0	1.5	30	50													2.0				B365120	283.46	284.29	**0.857**			VA05082695	0.83
1	6	1.0	1.0	85														60.0											
5	1	2.0	5.5	40		2.0	q/s	3			6.0								2.0			B365121	284.29	284.99	**0.728**			VA05082695	0.70
5	1	2.0	5.5	40		2.0	q/s	3			6.0								2.0			B365122	284.29	284.99	**0.363**	DUP		VA05082695	0.70
7	1	1.5	7.0	50		4.0	q/s/cb	4			5.0							1.0		0.1		B365123	284.99	286.51	**0.343**			VA05082695	1.52
1	1	1.5	1.5	35		2.0	q/s	2			0.1							0.1		0.1		B365124	286.51	287.53	**0.119**			VA05082695	1.02
2	6	1.0	2.0	50														80.0											
4	1	0.5	2.0	70		1.0	q/s	2			0.1											B365125	287.53	288.39	**0.296**			VA05082695	0.86
3	1	1.2	2.6	50		2.0	cb/s	3			2.0							0.1		0.1		B365126	288.39	289.56	**0.112**			VA05082695	1.17
2	4	0.6	1.0	70		10.0	cb/s	4										4.0											

DRILL LOG LEGEND P1	DATE: September 4 - 8, 2005	PAGE 13 of 14	
DRILL HOLE # : DG05-307C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
				EOH						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 4 - 8, 2005

LOGGED BY: Melodie Stone

PAGE 14 of 14

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments?	CSV	Width
						Selvages				Sulphides								Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
4	1	1.0	2.3	60		6.0	cb/s	4			3.0											B365127	289.56	291.08	**0.035**			VA05082695	1.52
																						EOH							

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-308C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1115m

BEARING: 000 | DIP: -50°

DATES DRILLING: August 24 - Sept. 1, 2005

DATES LOGGING: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

COORD SYSTEM: NAD 27: EASTING: 459956 NORTHING: 7099086

COORD SYSTEM: NAD 83: EASTING: 459837 NORTHING: 7099271

NAD 27 (CORRECTED for historic grid): EASTING: 459926 NORTHING: 7099096

SECTION LINE(historic grid)

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ

Overburden:

Deviation:

Casing: 6.10 m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0.00	6.10	CASING
6.10	27.43	MSED
27.43	34.30	HFLS
34.30	299.31	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B365548 - B365697

Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05

Lab Record #: VA05083821 Date Received: 28-Sept-05

Sample Sequence: B365698 - B365794

Requisition #: MASP448STRGOL.05Q Date Shipped: 16-Sept-05

Lab Record #: VA05083822 Date Received: 28-Sept-05

Duplicates:	B365562, B365582, B365602, B365622, B365642, B365662, B365682, B365702, B365722, B365742, B365762, B365782
Preparation Duplicate/ Check Assay:	B365549, B365569, B365589, B365609, B365629, B365649, B365669, B365689, B365709, B365729, B365749, B365769, B365789
Standards:	B365550 (1A), B365570 (3C), B365590 (4D), B365610 (5E), B365630 (1A), B365650 (6F), B365670 (3C), B365690 (7G), B365710 (2B), B365730 (5E), B365750 (4D), B365770 (3C), B365790 (2B)
Blanks:	B365556, B365576, B365596, B365616, B365636, B365656, B365676, B365696, B36555716, B365736, B365756, B365776

DEPTH (m)	AZI (Orig)	DIP (Orig)	AZ (+26 Corr)	AZ (+27 Corr)
54.9	331.7	48.2	357.7	358.7
115.8	332.1	49.7	358.1	359.1
207.3	333.0	48.0	359.0	360.0
298.7	332.2	44.3	358.2	359.2

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND - P1	DATE: September 6 - 11, 2005	PAGE 1 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
1	0-6.10	0.00	6.10	Casing. No recovery.						
80	6.10-27.43	6.10	27.43	MSED are very broken up and frac'd with poor recovery. Frac faces are lim with mnr cb. MSED's interchange between silicified bio and grey qtz fol'd MSED and non-silicified dark bio-rich, soft, white, randomly orientated, euhedral laths. QV's are common but with no fresh mineralization observed (2% ox'd vugs). Interval 7.62-9.14m is one broken up qv (sampled B365548). Silicified core is more abundant. Fresh bio blebs occur locally in bio-rich, soft core. Foliations: 9.44m at 30°, 11.90m at 45°, 13.40m at 60°, 14.50m at 50°, 15.54m at 60°, 18.00m at 60°, 24.20m at 45°.	2					
81	27.43-34.30	27.43	34.30	MSED; HFLS is heavily frac'd and much more lim than previous interval. Core is dark, soft, bio-rich and very fine grained and foliated. Qv's x-cutting fol'n have fingered into the fol'ns. Very fine grained soft white minerals speckled through out. Contact with GND is between 33.53 and 35.05 (crumbled sub-rounded core). From 33.23-33.53m core is extremely clay alt'd (flt gg?) and lim. Foliations: 28.76m at 45°, 29.15m at 30°, 29.47m at 45°, 30.20m at 50°, 31.80m at 45°.	4					
10	34.30-299.31	34.20	49.20	GND is typical as seen in previous holes. GND has been mod ox'd with lim and cc/cb on frac faces. Core is very frac'd and broken up with comp pieces up to 35 cm (5x4x3 cm avg.). Locally core is mod cb alt'd from 39.98-40.17 m). Rare dark grey-black blebs that are fairly hard (~5) with v.f.g. specs (Aspy?) within qv's. Where ox'n is most intense, may have been previously ser alt'd as darker red-brown grains are very soft and non-cb. Slickenlines: 41.80m face 30°, lines 70°.	3					
10		49.20	62.48	GND is extensively clay alt'd through out and lim. Cb alt'n is also mod through out. GND is extensively weathered as, locally, core crumbles into sand (56.30-56.40). No shearing observed. Contact with non-clay alt'd GND is abrupt but crumbled. Qv'ing is minor and commonly displaced by frac's. Slickenlines: 52.12m face 30° lines 5°, at 62.00m face 5° lines 85°.	4			5	3	
10		62.48	112.78	GND is mod ox'd through out interval. Cb/cc frac's/frac filling is abundant through out core. Qv's tend to be heavily frac'd by cb (lim) frac's. Qv's are vuggy with lim staining (weathered sulphides). Silicified GND occurs locally at 62.88-63.38m with sharp contact to GND at 5° and is bery ox'd and vuggy. MGD bleb (74.52-74.60m) with frac'd contact and x-cut by qv's (mm-scale). From 83.92-84.31m core is very clay alt'd and cb-rich and lim with contacts at 45°. From 96.45-96.65m dark bio-rich MSED blocks are subangular. Fol'n occurson blocks (3x3x3 cm avg.) but no full diameter MSED core is present and can't be measured. Qv of unknown thickness occurs (>2cm). Qv is white with no mineralization. Slickenlines: 70.60m face 5° lines 80°, at 76.20m face 40° lines 30°, at 76.70m face 50° lines 80°, at 79.55m face 30° lines 40°, at 95.51m face 45° lines 60°, at 104.40m face 15° lines 60°, at 104.60m face 45° lines 5°, at 111.45m face 30° lines 60°, at 111.60m face 10° lines 80°, at 112.48m face 65° lines 65°.	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	PAGE	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
1	1	152.0	152.0	?														1.0				B365548	7.62	9.14	**0.006**			VA05083821	1.52
1	1	152.0	152.0	?														1.0				B365549	7.62	9.14	**0.006**	PD/CA		VA05083821	1.52
																						B365550	STANDARD 1A		**0.888**	1A		VA05083821	
1	1	2.0	2.0	45														2.0					9.14	10.67					1.53
1	1	3.0	3.0	60														1.0					15.24	16.76					1.52
0																						B365551	27.43	28.96	**2.890**			VA05083821	1.53
1	1	0.8	0.8	60														1.0				B365552	28.96	30.48	**0.064**			VA05083821	1.52
0																						B365553	30.48	32.00	**0.053**			VA05083821	1.52
0																						B365554	32.00	33.53	**1.225**			VA05083821	1.53
1	1	2.0	2.0	30														1.0				B365555	35.05	36.58	**0.195**			VA05083821	1.53
																						B365556	BLANK		**<0.005**			VA05083821	
1	1	1.0	1.0	30														1.0				B365557	36.58	38.10	**0.021**			VA05083821	1.52
1	1	0.8	0.8	60														1.0				B365558	38.10	39.62	**0.034**			VA05083821	1.52
1	1	1.0	1.0	35														1.0				B365559	39.62	41.15	**0.526**			VA05083821	1.53
1	1	0.8	0.8	35									0.1					1.0				B365560	41.15	42.67	**0.059**			VA05083821	1.52
1	1	0.8	0.8	35														1.0				B365561	42.67	44.20	**0.816**			VA05083821	1.53
																						B365562	42.67	44.20	**0.045**	DUP		VA05083821	1.53
3	1	0.5	1.5	35	70													2.0				B365563	44.20	45.72	**0.246**			VA05083821	1.52
2	1	0.7	1.2	35														2.0				B365564	45.72	47.24	**0.050**			VA05083821	1.52
0																						B365565	47.24	49.20	**0.041**			VA05083821	1.96
0																						B365566	49.20	50.29	**0.033**			VA05083821	1.09
0																						B365567	50.29	51.82	**1.030**			VA05083821	1.53
1	1	0.5	0.5	60														2.0				B365568	51.82	53.34	**0.066**			VA05083821	1.52
1	1	0.5	0.5	60														2.0				B365569	51.82	53.34	**0.049**	PD/CA		VA05083821	1.52
																						B365570	STANDARD 3C		**0.092**	3C		VA05083821	
1	1	0.5	0.5	60														2.0				B365571	53.34	54.86	**0.053**			VA05083821	1.52
1	6	0.3	0.3	40														99.0											
0																						B365572	54.86	56.39	**0.068**			VA05083821	1.53
1	1	1.0	1.0	30														2.0				B365573	56.39	57.91	**0.074**			VA05083821	1.52
0																						B365574	57.91	59.44	**0.055**			VA05083821	1.53
2	1	1.0	1.2	30														2.0				B365575	59.44	60.96	**0.257**			VA05083821	1.52
																						B365576	BLANK		**<0.005**			VA05083821	
1	1	0.2	0.2	30														1.0				B365577	60.96	62.48	**0.490**			VA05083821	1.52
1	1	0.7	0.7	50														2.0				B365578	62.48	64.01	**0.576**			VA05083821	1.53
1	3	0.3	0.3	5																80.0									
2	1	1.2	1.8	50														5.0				B365579	64.01	65.53	**0.143**			VA05083821	1.52
0																						B365580	65.53	67.06	**0.292**			VA05083821	1.53
3	1	0.5	1.2	60	30								0.1					2.0				B365581	67.06	68.58	**0.159**			VA05083821	1.52
3	1	0.5	1.2	60	30								0.1					2.0				B365582	67.06	68.58	**0.237**	DUP		VA05083821	1.52

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 3 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		112.78	125.06	GND is mod ox'd through out. Locally core is extremely ox'd and slightly cb (117.96-118.47). Extremely ox'd core is also slightly clay alt'd and full diameter core within interval are 2 massive py vn's with black sulphide (?). core is heavily frac'd through out interval. Stains with lim and cb in frac's are less common than previous intervals. Extremely clay alt'd core occurs locally at 118.95-119.08m. Frac'd blocks commonly have slickenlines but cannot be measured. Slickenlines: 114.20m face 10° lines 45°, at 115.72m face 50° lines 40°, at 121.03m face 30° lines 80°, at 124.40m face 45° lines 85°.	3					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
5	1	0.6	2.2	50		1.5	S	5	2				0.1					5.0				B365583	68.58	70.10	0.478			VA05083821	1.52
1	1	0.8	0.8	45						0.1								1.0				B365584	70.10	71.63	0.166			VA05083821	1.53
1	1	0.2	0.2	45														1.0				B365585	71.63	73.15	0.140			VA05083821	1.52
6	1	0.5	2.8	45	70																	B365586	73.15	74.68	0.605			VA05083821	1.53
2	1	0.3	0.5	50														2.0		2.0		B365587	74.68	76.20	0.059			VA05083821	1.52
1	1	0.5	0.5	50														2.0				B365588	76.20	77.72	0.068			VA05083821	1.52
1	1	0.5	0.5	50														2.0				B365589	76.20	77.72	0.035	PD/CA		VA05083821	1.52
																						B365590	STANDARD 4D		0.450	4D		VA05083821	
2	1	1.0	1.5	45														2.0				B365591	77.72	79.25	0.368			VA05083821	1.53
1	1	0.3	0.3	45														1.0				B365592	79.25	80.77	0.546			VA05083821	1.52
2	1	1.0	1.5	45														2.0				B365593	80.77	82.30	0.600			VA05083821	1.53
0																						B365594	82.30	83.82	1.480			VA05083821	1.52
1	1	0.5	0.5	45		0.5	S	5	3									2.0				B365595	83.82	85.34	0.094			VA05083821	1.52
																						B365596	BLANK		<0.005			VA05083821	
3	1	0.5	1.4	45	30	0.4	S	4	3													B365597	85.34	86.87	0.522			VA05083821	1.53
3	1	1.5	2.3	50														1.0				B365598	86.87	88.39	0.889			VA05083821	1.52
8	1	2.0	5.4	50	45	0.5	S	5	3									2.0				B365599	88.39	89.92	0.848			VA05083821	1.53
1	5	0.4	0.4	50		0.3	Q	5	3									5.0											
4	1	2.0	4.0	50		1.0	S	5	3	1.0								2.0				B365600	89.92	91.44	1.030			VA05083821	1.52
0																						B365601	91.44	92.96	0.141			VA05083821	1.52
0																						B365602	91.44	92.96	0.145	DUP		VA05083821	1.52
4	1	0.6	1.5	50														2.0				B365603	92.96	94.49	0.084			VA05083821	1.53
2	1	0.5	0.9	50														1.0				B365604	94.49	96.01	0.239			VA05083821	1.52
1	1	0.3	0.3	50														1.0				B365605	96.01	96.45	0.038			VA05083821	0.44
1	1	2.0	2.0	?																		B365606	96.45	96.65	0.020			VA05083821	0.20
2	1	1.2	1.6	50		0.5	S	5	3													B365607	96.65	97.54	0.692			VA05083821	0.89
2	1	0.5	1.0	50														1.0				B365608	97.54	99.06	0.401			VA05083821	1.52
2	1	0.5	1.0	50														1.0				B365609	97.54	99.06	0.288	PD/CA		VA05083821	1.52
																						B365610	STANDARD 5E		1.460	5E		VA05083821	
5	1	1.5	5.5	50	40	1.0	S	5	4									1.0				B365611	99.06	100.58	0.169			VA05083821	1.52
2	1	0.3	0.5	50														1.0				B365612	100.58	102.11	0.110			VA05083821	1.53
3	1	0.8	1.7	60	50													1.0				B365613	102.11	103.63	0.093			VA05083821	1.52
1	5	0.5	0.5	50		0.5	S/Q	4	1													B365614	103.63	105.16	0.425			VA05083821	1.53
3	1	2.0	2.8	50														2.0											
2	3	0.3	0.6	50						5.0							0.1	10.0									Mo		
4	1	0.7	2.0	50		3.0	Chl	4	2				0.1					1.0				B365615	105.16	106.68	0.309			VA05083821	1.52
																						B365616	BLANK		<0.005			VA05083821	
3	1	0.5	1.1	45	50	1.0	S	4	2	2.0								2.0				B365617	106.68	108.20	0.047			VA05083821	1.52
8	1	2.5	8.5	60	50													2.0				B365618	108.20	109.73	0.290			VA05083821	1.53
4	1	0.5	1.9	50	40													2.0				B365619	109.73	111.25	0.232			VA05083821	1.52
2	1	2.5	4.5	60		0.8	S	3	2				0.1					2.0				B365620	111.25	112.78	0.849			VA05083821	1.53
8	1	2.0	7.5	60	50					0.1								2.0				B365621	112.78	114.30	0.117			VA05083821	1.52
8	1	2.0	7.5	60	50					0.1								2.0				B365622	112.78	114.30	0.211	DUP		VA05083821	1.52
3	1	1.4	2.8	50	60								0.1					1.0				B365623	114.30	115.82	0.084			VA05083821	1.52
0																						B365624	115.82	117.35	0.209			VA05083821	1.53
1	1	2.0	2.0	50														1.0				B365625	117.35	117.96	0.409			VA05083821	0.61
2	6	1.0	1.5	65						50.0			40.0									B365626	117.96	118.47	0.714			VA05083821	0.51
1	1	0.5	0.5	45																		B365627	118.47	118.87	0.522			VA05083821	0.40
0																						B365628	118.87	120.40	0.075			VA05083821	1.53
0																						B365629	118.87	120.40	0.087	PD/CA		VA05083821	1.53
																						B365630	STANDARD 1A		0.806	1A		VA05083821	
0																						B365631	120.40	121.92	0.036			VA05083821	1.52
4	1	3.0	8.0	50														1.0				B365632	121.92	123.44	0.284			VA05083821	1.52
6	1	3.0	9.0	70	60																	B365633	123.44	125.06	0.246			VA05083821	1.62

DRILL LOG LEGEND - P1	DATE: September 6 - 11, 2005	PAGE 5 of 12	
DRILL HOLE # : **DG05 - 308C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		125.06	128.02	GND is intensely ox'd mod frac'd (8 cm avg) and, for the most part, comp. Small intervals exist where core gradually fades into slightly ox'd, ser alt'd GND and then back into less ox'd GND (4). Possibly, intensely alt'd core was previously ser alt'd GND(?). Fresh ser alt'd GND occurs locally from 125.70-125.75m with sharp contacts at 60°. Clay alt'n occurs at uphole contact for 20 cm. Down hole contact fades into rel unalt'd GND with abundant lim frac selvages.	5	5				
10		128.02	137.31	GND is, for the most part, mod ox'd. Intervals of nearly unox'd GND are common (up to 30 cm) with sharp frac'd +/- slip contacts. Core is mod frac'd (8 cm avg). Cb/cc is common in/on frac's. At 128.74m within 12 cm qv is deep purple staining (Hem?) with massive py at edge of vn. Slickenlines: 129.15m face 45° lines 85°, at 131.92m face 45° lines 60°, at 138.30m face 15° lines 80°.	3					
10		137.31	153.92	GND appears fresh. Ox'n occurs as salveges along cb and lim frac's. However, GND is highly ox'dlocally with sharp contacts to fresh GND. GND is very slightly ser alt'd through out. At 141.05m a 1.2 cm qz/py vn (at 45° with 20% py) is sheared (multiple fracs and dissplacements) with 1.2 cm dextral dissplacement at 30°. The qv is also stretched into shear zone. Shear zone ~7 cm wide. Slickenlines are present at edge of shear zone: face 60° lines 2°. Within shear zone, ser alt'n is more intense (3). Another clay-rich shear zone at 145.07-145.12m present with fol'n at 70° and with slickenlines in two directions on the same face: 85° and 75°. From 145.12-146.60m core is heavily frac'd (no full diameter core) and highly ox'd. From 146.60-147.39m core is intensly ser alt'd with 4 dark red-brown (ox'd) cb-rich frac salveges at 30°. From 144.78-145.07m core is slightly ser and clay alt'd (lighter colour) with 5.5cm qz-po vn.Slip faces commonly have py smearing. Slickenlines are abundant through out. Slickenlines: 138.00m face 70° lines 70°, at 139.40 face 50° lines 50°, at 140.55 face 5° lines 50°, at 142.00m face 40° lines 45°, at 143.50m face 10° lines 30°, at 145.90m face 60° lines 20°, at 15	2	1				
10		153.92	161.27	GND is ox'd throughout and is heavily fractured (cm-scale blocks). fracs are 1mm, commonly w/ cb/cc.	2					

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

PAGE 6 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL													Interval					
						Selvages				Sulphides								Oxidation				Sample Number			Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
1	1	4.0	4.0	60														2.0				B365634	125.06	126.49	1.405			VA05083821	1.43
1	1	1.0	1.0	45														1.0				B365635	126.49	128.02	0.174			VA05083821	1.53
																						B365636	BLANK		<0.005			VA05083821	
4	1	1.2	2.5	45	80												0.1	2.0				B365637	128.02	128.58	0.157		Mo	VA05083821	0.56
1	1	12.0	12.0	45														1.0				B365638	128.58	128.70	6.900			VA05083821	0.12
1	1	0.5	0.5	50														1.0				B365639	128.70	129.54	0.103			VA05083821	0.84
4	1	1.2	4.0	45														1.0				B365640	129.54	131.06	0.090			VA05083821	1.52
2	1	2.0	3.0	45														1.0				B365641	131.06	132.59	0.149			VA05083821	1.53
2	1	2.0	3.0	45														1.0				B365642	131.06	132.59	0.137	DUP		VA05083821	1.53
1	1	0.2	0.2	30														1.0				B365643	132.59	134.11	0.140			VA05083821	1.52
3	1	3.0	4.1	45	60					1.0								2.0				B365644	134.11	135.88	0.418			VA05083821	1.77
1	1	27.0	27.0	35						1.0			0.1					2.0				B365645	135.88	136.15	9.660			VA05083821	0.27
3	1	0.4	1.0	50																		B365646	136.15	137.31	0.235			VA05083821	1.16
1	6	0.2	0.2	40		0.5	Q	4	1	50.0			5.0					10.0											
4	1	1.6	2.4	45	70	1.0	Q/S	5		2.0	2.0		0.1				0.1	1.0				B365647	137.31	138.68	0.052		Mo	VA05083821	1.37
1	3	0.5	0.5	45		0.5	Q/S	4	3																				
4	1	0.6	1.6	45		0.3	q	5		0.1	2.0		0.1									B365648	138.68	140.21	0.063			VA05083821	1.53
4	1	0.6	1.6	45		0.3	q	5		0.1	2.0		0.1									B365649	138.68	140.21	0.050	PD/CA		VA05083821	1.53
																						B365650	STANDARD 6F		2.650	6F		VA05083821	
3	1	1.0	2.0	45							2.0							1.0				B365651	140.21	141.73	0.179		sheared qtz vn/py	VA05083821	1.52
1	6	1.2	1.2	45						25.0																			
1	1	1.8	1.8	45														1.0				B365652	141.73	143.26	0.063			VA05083821	1.53
0																						B365653	143.26	143.66	0.018			VA05083821	0.40
0																						B365654	143.66	144.78	0.315			VA05083821	1.12
1	1	5.5	5.5	50						2.0	10.0	0.1	0.1									B365655	144.78	145.07	1.670			VA05083821	0.29
																						B365656	BLANK		<0.005			VA05083821	
4	1	2.0	3.6	50													0.1					B365657	145.07	146.60	0.462		Mo	VA05083821	1.53
4	1	0.4	1.4	50						1.0												B365658	146.60	147.39	0.682			VA05083821	0.79
3	1	1.2	1.8	50		0.5	5	4	3													B365659	147.39	148.20	1.100			VA05083821	0.81
4	1	0.4	1.6	50	85	1.6	s	5	1											1.0		B365660	148.20	149.35	0.851			VA05083821	1.15
5	1	0.5	2.0	45		1.0	s	4			1.0	0.1										B365661	149.35	150.88	0.192			VA05083821	1.53
5	1	0.5	2.0	45		1.0	s	4			1.0	0.1										B365662	149.35	150.88	0.743	DUP		VA05083821	1.53
2	1	4.0	5.0	50									0.1									B365663	150.88	152.40	0.773			VA05083821	1.52
5	1	3.0	45.0	45							1.0	0.1										B365664	152.40	153.92	2.740			VA05083821	1.52
5	1	2.0	3.5	45		0.3	q	5		0.1			0.1				0.1					B365665	153.92	155.45	0.137		Mo	VA05083821	1.53
7	1	2.0	5.0	45		0.4	s	4				0.1					0.1	1.0				B365666	155.45	156.97	1.485		Mo	VA05083821	1.52
2	1	2.0	2.5	45						1.0								1.0				B365667	156.97	158.50	0.072			VA05083821	1.53
2	1	1.4	1.8	45						1.0								1.0				B365668	158.50	160.02	0.237			VA05083821	1.52
1	5	0.3	0.3	45														1.0											
2	1	1.4	1.8	45						1.0								1.0				B365669	158.50	160.02	0.140	PD/CA		VA05083821	1.52
1	5	0.3	0.3	45														1.0											
																						B365670	STANDARD 3C		0.090	3C		VA05083821	
2	1	0.5	1.0	45																		B365671	160.02	161.27	0.185			VA05083821	1.25

DRILL LOG LEGEND P1	DATE: September 6 - 11, 2005	PAGE 7 of 12	
DRILL HOLE # : DG05 - 308C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	GEOLOGICAL DESCRIPTION				ROCK (Alteration)					
	From → To:	From:	To:	Comments:	Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		161.27	182.88	grey GND that's very slightly ser +/- chl alt'd throughout. core is v.comp throughout. locally core is heavily fractured and lim from 166.12-167.50m. shear zone occurs at 167.35m (3-5cm) w/ foliations at 40°. frac faces/fills are still lim commonly w/ cb/cc. non-ox'd fracs do occur but are rare and commonly contain fresh po w/ tr cpy. qtz vn generally contain 1-10% chl (not classified as qtz/chl vns-5). slickenlines: at 163.84m face 50° lines 60°; at 164.95m face 60° lines 50°; at 167.75m face 45° lines 80°; at 173.64m face 60° lines 80°; at 182.78m face 60° lines 90°.		1				
10		182.88	198.12	GND similar to interval 161.27-182.88m as previously described. large intervals of intense ser alt is common. where ser alt'd GND is in contact w/ rel unalt'd GND there tends to be a transition zone of darker green alt (chl) from 1-4cm. from 185.51-185.99m, 2 large qtz vns (19 & 17cm). Slickenlines: 193.57m face 15° lines 40° at 193.63m face 40° lines 40°.	1					
10		198.12	208.79	GND is very slightly ser alt'd through out. Core is comp. Frac's / frac fills are cb and ser +/- chl. Lim is no longer observed within frac's.		1				
10		208.79	211.84	Grey GND that has been mod clay alt'd and slightly ser alt'd. Up hole contact is gradual. At 211.45-211.84m GND is silicified with a shallow (15°), sharp contact. Qv's tend to be irregular +/- displaced (no fol'n). Slickenlines: 209.25m face 45° lines 85° at 211.12m face 5° lines 70°, at 211.65m face 30° lines 60°.		2		3		

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrholite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
7	1	2.0	8.5	45		0.6	q/s	5	1		0.1						0.1					B365672	161.27	163.07	0.096		Mo	VA05083821	1.80
4	1	2.3	3.8	45	65	0.5	s	3														B365673	163.07	164.59	0.034			VA05083821	1.52
2	1	0.3	0.6	45		4.0	q/s/chl	5		1.0	1.0											B365674	164.59	166.12	0.163		py found w/in cb bleb	VA05083821	1.53
0																						B365675	166.12	167.64	0.603			VA05083821	1.52
																						B365676	BLANK		<0.005			VA05083821	
2	1	0.5	0.9	45		0.4	S/Q	3			1.0	0.1	0.1							2.0		B365677	167.64	169.16	0.067			VA05083821	1.52
2	1	1.5	1.7	45		1.2	q/chl	5			1.0		1.0									B365678	169.16	170.69	0.098			VA05083821	1.53
1	5	0.2	0.2	40							2.0																		
1	1	0.3	0.3	45																		B365679	170.69	172.21	0.023			VA05083821	1.52
3	1	0.7	1.6	45		0.2	q	5			4.0	0.1										B365680	172.21	173.74	0.046			VA05083821	1.53
8	1	2.0	6.5	45	45	0.4	q	5			4.0	0.1					0.1					B365681	173.74	175.26	0.050		qtz vn at 45°; x-cut qtz vn at 135°; 0.1 qp	VA05083821	1.52
8	1	2.0	6.5	45	45	0.4	q	5			4.0	0.1					0.1					B365682	173.74	175.26	0.021	DUP	qtz vn at 45°; x-cut qtz vn at 135°; 0.1 mo	VA05083821	1.52
3	1	0.6	1.5	45		0.4	s/q	5			4.0		0.1				0.1					B365683	175.26	176.78	0.038		Mo	VA05083821	1.52
2	5	0.2	0.2	45		0.3	q	5			5.0		0.1																
6	1	1.4	3.0	45		0.4	q	5			5.0	0.1	0.1				0.1			1.0		B365684	176.78	178.31	0.042		Mo	VA05083821	1.53
3	1	0.4	1.0	45	40	0.3	q	5			4.0	1.0										B365685	178.31	179.83	0.129			VA05083821	1.52
2	1	0.4	0.8	45		0.4	q/chl	5			2.0											B365686	179.83	181.36	0.021			VA05083821	1.53
2	1	1.0	1.4	45							4.0	1.0										B365687	181.36	182.88	0.716			VA05083821	1.52
5	1	2.0	3.4	45	30	0.3	q	5			4.0	0.1										B365688	182.88	184.40	0.452			VA05083821	1.52
5	1	2.0	3.4	45	30	0.3	q	5			4.0	0.1										B365689	182.88	184.40	0.547	PD/CA		VA05083821	1.52
																						B365690	STANDARD 7G		4.370	7G		VA05083821	
6	1	1.2	2.4	40	50					1.0	2.0		1.0									B365691	184.40	185.51	0.197		Mo	VA05083821	1.11
2	1	19.0	36.0	50	35					12.0	2.0		5.0	1.0	2.0		0.1					B365692	185.51	185.99	9.350			VA05083821	0.48
7	1	2.0	5.0	40	50					2.0			0.1									B365693	185.99	187.02	0.557			VA05083821	1.03
1	1	0.2	0.2	45							2.0											B365694	187.02	187.97	0.251			VA05083821	0.95
3	1	0.5	1.2	45							1.0						0.1					B365695	187.97	188.98	0.153		Mo	VA05083821	1.01
																						B365696	BLANK		<0.005			VA05083821	
5	1	1.0	2.1	45		1.0	S/Q	5		0.1	1.0											B365697	188.98	190.50	0.036			VA05083821	1.52
1	5	1.0	1.0	45		0.3	Q/CHL	5																					
4	1	1.2	3.8	45		1.5	Q/CHL	5		0.1	1.0											B365698	190.50	192.02	0.041			VA05083822	1.52
2	1	0.8	1.3	45		1.0	Q/S	5			2.0	0.1										B365699	192.02	192.85	0.287			VA05083822	0.83
1	6	2.5	2.5	45						2.0			2.0		2.0							B365700	192.85	193.04	0.493			VA05083822	0.19
4	1	3.0	4.5	45	30	2.0	S/CHL	5		0.1	2.0											B365701	193.04	194.35	0.443			VA05083822	1.31
4	1	3.0	4.5	45	30	2.0	S/CHL	5		0.1	2.0											B365702	193.04	194.35	0.244	DUP		VA05083822	1.31
1	1	0.3	0.3	45		0.2	A/Q	5			2.0											B365703	194.35	195.86	0.018			VA05083822	1.51
3	1	2.5	3.5	5	45					0.1	1.0	0.1					0.1			0.1		B365704	195.86	197.48	0.015		Mo	VA05083822	1.62
3	1	1.0	2.0	50	10						1.0											B365705	197.48	198.12	0.524			VA05083822	0.64
4	1	0.5	1.5	45	30						1.0											B365706	198.12	199.64	0.048			VA05083822	1.52
6	1	1.0	3.1	40							2.0											B365707	199.64	201.17	0.106			VA05083822	1.53
1	1	0.6	0.6	45		0.3	Q/S	5			4.0	0.1					0.1					B365708	201.70	202.69	0.111		Mo	VA05083822	0.99
1	1	0.6	0.6	45		0.3	Q/S	5			4.0	0.1					0.1					B365709	201.70	202.69	0.123	PD/CA		VA05083822	0.99
																						B365710	STANDARD 2B		3.000	2B		VA05083822	
5	1	0.6	2.2	40		0.5	Q/S	5			3.0	0.1										B365711	202.69	204.22	0.026			VA05083822	1.53
4	1	0.5	2.4	35		1.0	Q/S	5			4.0	0.1										B365712	204.22	205.74	0.156			VA05083822	1.52
5	1	4.0	9.5	35		0.5	S	5			2.0						Mo/.1					B365713	205.74	207.26	0.592			VA05083822	1.52
1	3	0.5	0.5	40		0.5	Q/S	5		0.1	1.0																		
4	1	1.0	2.5	40		1.0	Q/S	5			4.0											B365714	207.26	208.79	0.127			VA05083822	1.53
1	1	0.5	0.5	45																		B365715	208.79	210.31	0.033			VA05083822	1.52
																						B365716	BLANK		<0.005			VA05083822	
0																						B365717	210.31	211.84	0.163			VA05083822	1.53

DRILL LOG LEGEND - P1	DATE: September 6 - 11, 2005	PAGE 9 of 12	
DRILL HOLE # : DG05 - 308C	FeOx 0 = Unoxidized 5 = Intensely Ox'd	Ser, Chl, etc 0 = Unaltered 5 = Intensely Altered	Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		211.84	233.76	Grey GND has been very slightly ser alt'd. Core is comp. Frac's / frac faces contain cb/cc and ser. Locally frac'ing is more abundant (ie. 222.50-225.55m). Diss py and smeared py are common on frac faces and slip faces (with Chl). At 211.77m a 0.5 cm qv shows 1 cm sinistral displacement along a 2° cb/ser frac. At 218.11m a 30° cc frac contains 20% Po and 2% Cp. mm-scale stringers of qtz-chl-po are common. Slickenlines: 213.30m face 5° lines 80°, at 218.60m face 5° lines 80°, at 223.40m face 30° lines 50°, at 224.13m face 50° lines 10°, at 228.20m face 20° lines 20°.		1				
10		233.76	239.27	GND is intensely ser alt'd except for minor intervals of mod ser alt'd GND. Mod clay alt'n occurs locally from 234.28-238.41m and contains fine grained, euhedral diss py (5%). QV within interval is softer and slightly irregular. Slickenlines tend to be distinct with smeared py. Diss py occurs through out ser alt'd core ~1% along with a trace of aspy. QV are commonly displaced (up to 1.5 cm) by shallow frac's. Slickenlines: 235.01m face 80° lines 80°, at 235.11m face 20° lines 85°, at 236.25m face 10° lines 60°, at 236.64m face 45° lines 2° at 237.45m face 30° lines 85°.		5				
10		239.27	251.46	Grey GND is very slightly ser +/- chl alt'd. Intense ser alt'd core occurs locally [5] (up to 33cm). Intense ser alt. appears to be associated with fracturing (pre-qv) and qv develop within fractures as ser selvages are of different thickness on either side of qv and fractures are adjacent to qv. MGD occurs from 249.70-250.29 and is f.g. MGD also appears ser alt'd throughout. contact with grey GND is gradual. 1-2mm vnlts with 1-10% chl are common and tent to be po +/- aspy-rich (10-20%). F-mg euhedral and smeared py common on fracture and slip faces. Slickenlines: at 243.25m face 45° lines 75°, at 244.65m face 15° lines 45°, and at 249.12m face 5° lines 30°. At 245.26m a felsic dyke (2.5cm) cuts through GND at 15%. Dyke is qtz rich with 5° f.g. bio x-cut by qv.		1	1			
10		251.46	272.23	Grey GND is slightly clay alt'd and very slightly ser alt'd. Plag grains are abundant and are soft and white. Core is highly fractured (cb/cc filled with ser). Q.V.s tend to be highly fractured (cc) commonly with mm-scale displacement. QV also tend to have 0-10% chl. Blocks of very slightly ser/chl alt'd GND occur with slip faces on contacts. Slickenlines: at 254.10m face 40° lines 75°, at 257.16m face 10° lines 30°, at 257.36m face 60° lines 5°, at 265.15m face 20° lines 60°, at 270.00m face 40° lines 70°, and at 271.01m face 20° lines 45°.		1		2		

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2006

LOGGED BY: Kevin Piepgrass

PAGE 10 of 12

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides								Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	PAGE	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
3	1	0.5	1.5	30	40	1.2	S	5			1.0											B365718	211.84	213.36	**0.060**			VA05083822	1.52
1	5	0.6	0.6	30		0.5	S/Q	5		0.1	1.0																	
4	1	1	1.7	30		0.3	Q	5			4											B365719	213.36	214.88	**0.069**			VA05083822	1.52
2	1	0.6	1.2	30		0.5	Q/S	5			4.0											B365720	214.88	216.41	**0.237**			VA05083822	1.53
3	1	1.0	1.8	30	35						3.0											B365721	216.41	217.93	**0.030**			VA05083822	1.52
3	1	1.0	1.8	30	35						3.0											B365722	216.41	217.93	**0.056**	DUP		VA05083822	1.52
2	1	1.0	1.5	45	30						2.0											B365723	217.93	219.46	**0.029**			VA05083822	1.53
2	1	0.6	1.1	35		1.0	s	5			4.0	1.0										B365724	219.46	220.98	**0.164**			VA05083822	1.52
4	1	1.0	2.8	35		1.0	q/s	5			2.0	0.1										B365725	220.98	222.50	**0.098**			VA05083822	1.52
1	1	0.4	0.4	35							1.0											B365726	222.50	224.03	**0.165**			VA05083822	1.53
4	1	0.4	1.3	35	45	0.5	s	5		0.1	2.0											B365727	224.03	225.55	**0.105**			VA05083822	1.52
2	1	0.4	7.0	35							3.0											B365728	225.55	227.08	**0.066**			VA05083822	1.53
2	1	0.4	7.0	35							3.0											B365729	225.55	227.08	**0.034**	PD/CA		VA05083822	1.53
																						B365730	STANDARD 5E		**1.335**	5E		VA05083822	
3	1	0.5	1.1	45	40	0.4	q/s	5		0.1	2.0											B365731	227.08	228.60	**0.504**			VA05083822	1.52
10	1	0.6	4.0	45	30					0.1	4.0						Mo/.1					B365732	228.60	230.12	**0.071**		A 5° qv x-cuts all vn's. 45° vn's are in ser alt'd core.	VA05083822	1.52
4	1	1.0	4.0	45	60						3.0											B365733	230.12	231.65	**0.337**			VA05083822	1.53
5	1	0.5	1.5	45	35						4.0											B365734	231.65	233.17	**0.274**			VA05083822	1.52
1	5	0.4	0.4	30							5.0											B365735	233.17	233.76	**0.037**			VA05083822	0.59
																						B365736	BLANK		**<0.005**			VA05083822	
8	1	0.7	2.7	45	30					8.0												B365737	233.76	234.70	**0.676**			VA05083822	0.94
3	1	0.5	1.3	45	60					2.0												B365738	234.70	236.22	**0.083**		Py in vn's occur in blebs	VA05083822	1.52
1	6	1.0	1.0	88						15.0	40.0				1.0													
5	1	1.0	3.1	45	60					1.0	2.0											B365739	236.22	237.74	**2.660**			VA05083822	1.52
1	6	1.7	1.7	55						50.0																		
6	1	0.8	3.0	45	30					0.1	2.0	0.1										B365740	237.74	239.27	**0.182**			VA05083822	1.53
5	1	5.0	6.0	45		1.0	s	5		1.0	3.0		1.0									B365741	239.27	240.79	**0.285**			VA05083822	1.52
5	1	5.0	6.0	45		1.0	s	5		1.0	3.0		1.0									B365742	239.27	240.79	**0.767**	DUP		VA05083822	1.52
7	1	1.0	2.8	45	30	1.0	s/q	5		1.0	5.0	1.0										B365743	240.79	242.32	**0.802**			VA05083822	1.53
2	6	2.0	2.3	55	45	0.5	q	5		15.0	5.0		20.0														po only in 0.3cm sx		
8	1	2.2	5.5	45		1.0	s/q	5		0.1	5.0	0.1										B365744	242.32	243.84	**0.074**			VA05083822	1.52
6	1	1.2	2.6	45		0.4	s	5			2.0	0.1										B365745	243.84	245.36	**0.369**			VA05083822	1.52
2	1	0.5	0.7	45		1.0	s	3			2.0	0.1	5.0									B365746	245.36	246.89	**0.030**		aspy only occurs in	VA05083822	1.53
4	1	0.5	1.8	45	10	1.0	s/q	4			2.0	0.1										B365747	246.89	248.41	**0.032**			VA05083822	1.52
3	1	0.6	1.3	45							2.0											B365748	248.41	249.70	**0.080**			VA05083822	1.29
3	1	0.6	1.3	45							2.0											B365749	248.11	249.70	**0.074**	PD/CA		VA05083822	1.59
																						B365750	STANDARD 4D			4D	SAMPLE???	VA05083822	
3	1	0.5	1.4	40		0.4	s	5			5.0	0.1	0.1									B365751	249.70	250.29	**0.375**			VA05083822	0.59
5	1	1.5	3.1	45							2.0	0.1										B365752	250.29	251.46	**0.104**			VA05083822	1.17
6	1	1.5	3.2	45	30	0.5	s	2			2.0											B365753	251.46	252.98	**0.057**			VA05083822	1.52
5	1	0.7	2.4	50		0.4	5	3			2.0	0.1										B365754	252.98	254.51	**0.068**			VA05083822	1.53
4	1	0.5	1.6	60							3.0											B365755	254.51	256.03	**0.058**			VA05083822	1.52

094878

DRILL LOG LEGEND - P1	DATE: September 6 - 11, 2005 PAGE 11 of 12	
DRILL HOLE # : DG05 - 308C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		272.23	277.20	GND is very slightly ser and chl alt'd. Core is competent. Up hole contact is gradual. Down hole contact is sharp (frac) at 40°. From 274.98-276.06m core is intensely ser alt'd. <2mm chl/po vnlts are common. Slickenlines: at 273.37m face 45° lines 30°, and at 275.18m face 60° lines 80°.		1	1			
10		277.20	294.50	GND same as previously described from interval 251.46-272.23m.Locally core is moderately clay alt'd (277.20-277.37m). Intense clay alt'd core from 277.20-277.37m contains diss, ox'd py (?). (Diss py has been observed in previous DDHs where clay alt'n is intense). From 280.99-281.45m core is intensely ser alt'd and also intensely clay alt'd. Q.V. are irregular and displaces (no shear fol'n observed). cb fracture at 15° displaces 2 avs by 5cm(293.53m). Slickenlines: at 277.45m face 5° lines 30°, at 280.80m face 20° lines 85°, at 282.45m face 5° lines 85°, at 287.11m face 30° lines 80°, at 288.34 face 50° lines 10°, at 292.00m face 20° lines 50°, and at 293.53m face 45°-10° (irregular) lines 85°.		1		2		
10		294.50	299.31	GND is very slightly ser and chl alt'd, same as previously described from interval 272.24-277.20m Slickenlines: at 295.43m face 65° lines 65°, and at 299.29m face 30° lines 75°.		1	1			
				EOH						

DRILL LOG LEGEND - P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 6 - 11, 2005

LOGGED BY: Kevin Piepgrass

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		PAGE	To					
																						B365756	BLANK		<0.005			VA05083822	
5	1	1.0	4.0	60							2.0		0.1									B365757	256.03	257.56	0.192			VA05083822	1.53
4	1	1.0	3.0	50	60	1.0	5	3			2.0											B365758	257.56	259.08	0.074			VA05083822	1.52
3	1	1.0	2.0	60							2.0	0.1										B365759	259.08	260.60	0.107			VA05083822	1.52
2	1	1.4	1.8	60						0.1	2.0	0.1										B365760	260.60	262.13	0.413			VA05083822	1.53
3	1	1.0	2.2	60							3.0	1.0										B365761	262.13	263.85	0.383			VA05083822	1.72
3	1	1.0	2.2	60							3.0	1.0										B365762	DUPLICATE		0.144	DUP		VA05083822	
3	1	1.4	2.3	60	50						2.0											B365763	263.85	265.18	0.048			VA05083822	1.33
5	1	0.5	2.0	60		0.5	s	3			2.0											B365764	265.18	266.70	0.081			VA05083822	1.52
3	1	4.0	4.8	60		0.5	s	4		0.1	2.0											B365765	266.70	268.22	0.588			VA05083822	1.52
4	1	0.6	1.6	60	30	1.0	s/q	5			1.0											B365766	268.22	269.75	0.031			VA05083822	1.53
2	1	1.0	1.4	60	30						1.0											B365767	269.75	271.27	0.031			VA05083822	1.52
6	1	1.0	3.0	60	45	1.0	s	2			3.0											B365768	271.27	272.23	0.215			VA05083822	0.96
6	1	1.0	3.0	60	45	1.0	s	2			3.0											B365769	271.27	272.23	0.275	PD/CA		VA05083822	0.96
																						B365770	STANDARD 3C		0.090	3C		VA05083822	
1	1	0.3	0.3	60							2.0	0.1										B365771	272.23	272.80	0.025			VA05083822	0.57
4	1	0.5	1.8	60	20						3.0	0.1										B365772	272.80	274.32	0.070			VA05083822	1.52
1	1	0.6	0.6	45							15.0	1.0	0.1									B365773	274.32	274.98	0.096			VA05083822	0.66
5	1	1.0	2.3	45	60					1.0	1.0											B365774	274.98	276.06	0.079			VA05083822	1.08
1	6	0.5	0.5	50						20.0																			
1	1	1.0	1.0	60							1.0											B365775	276.06	277.20	0.043			VA05083822	1.14
																						B365776	BLANK		<0.005			VA05083822	
2	1	0.5	0.9	45							1.0											B365777	277.20	278.89	0.044			VA05083822	1.69
0																						B365778	278.89	280.42	0.146			VA05083822	1.53
1	1	0.8	0.8	45																		B365779	280.42	281.94	0.104			VA05083822	1.52
1	1	0.4	0.4	50							1.0											B365780	281.94	283.46	0.162			VA05083822	1.52
3	1	0.4	1.1	60	50					0.1	1.0											B365781	283.46	284.99	0.032			VA05083822	1.53
1	6	0.3	0.3	60						20.0																			
3	1	0.4	1.1	60	50					0.1	1.0											B365782	283.46	284.99	0.020	DUP		VA05083822	1.53
1	6	0.3	0.3	60						20.0																			
2	1	0.5	0.7	60							2.0	0.1										B365783	284.99	286.51	0.023			VA05083822	1.52
0																						B365784	286.51	288.04	0.289			VA05083822	1.53
3	1	0.5	1.2	30	60	0.5	s	3			1.0	0.1										B365785	288.04	289.56	0.036			VA05083822	1.52
2	1	1.0	1.5	60		0.4	s	4			1.0											B365786	289.56	291.08	0.048			VA05083822	1.52
1	1	0.4	0.4	60							1.0											B365787	291.08	292.61	0.027			VA05083822	1.53
4	1	1.5	3.0	60							1.0											B365788	292.61	294.50	0.037			VA05083822	1.89
4	1	1.5	3.0	60							1.0											B365789	292.61	294.50	0.040	PD/CA		VA05083822	1.89
																						B365790	STANDARD 2B		2.920	2B		VA05083822	
1	1	0.6	0.6	50							0.1											B365791	294.50	295.66	0.129			VA05083822	1.16
2	1	0.7	1.0	60	50						1.0											B365792	295.66	297.18	0.122			VA05083822	1.52
3	1	1.0	2.0	60	40						1.0											B365793	297.18	298.70	0.027			VA05083822	1.52
2	1	1.0	2.0	45							1.0											B365794	298.70	299.31	0.100			VA05083822	0.61
																						EOH	EOH	EOH					

DRILL HOLE SUMMARY SHEET

HOLE NO.: DG05-309C

PROJECT: Dublin Gulch - 1735

GROUND ELEVATION: 1070m

BEARING: 000 | DIP: -50°

DATES DRILLING: September 1 - 8, 2005 | DATES LOGGING: September 8 - 12, 2005

COORD SYSTEM: NAD 27: EASTING: 459799 NORTHING: 7099237

COORD SYSTEM: NAD 83: EASTING: 459680 NORTHING: 7099422

NAD 27 (CORRECTED for historic grid): EASTING: 459769 NORTHING: 7099247

SECTION LINE (historic grid): 459775 E

LOGGED BY: Melodie Stone

CONTRACTOR: Britton Brothers

DRILLING DETAILS

Hole Diameter: HQ & NQ

Overburden:

Deviation:

Casing: 8.53m

Core Size: HQ

Cement (# Bags): 0

Plug Depth: N/A

Notes: No plug necessary.

FROM	TO	LITHOLOGY
0	8.53	Csg; No recovery
8.53	274.62	GND

FROM	TO	ALTERATION

FROM	TO	MINERALIZATION (Veins)

SAMPLING DETAILS

Sample Sequence: B365128-B365200, B365800-B365826

Requisition #: MASP448STRGOL.05Q | Date Shipped: 16-Sep-05

Lab Record #: VA05082983 | Date Received: 27-Sep-05

Sample Sequence: B365827-B365964

Requisition #: MASP448STRGOL.05Q | Date Shipped: 17-Sep-05

Lab Record #: VA05085049 | Date Received: 29-Sep-05

Duplicates:	365142; 365162; 365182; 365802; 365822; 365842; 365862; 365882; 365902; 365922; 365942; 365962
Preparation Duplicate/ Check Assay:	365129; 365149; 365169; 365189; 365809; 365829; 365849; 365869; 365889; 365909; 365929; 365949
Standards:	365130 (6F); 365150 (3C); 365170 (5E); 365190 (4D) 365810 (7G); 365830 (3C); 365850 (7G); 365870 (1A); 365890 (5E); 365910 (4D); 365930 (7G); 365950 (2B)
Blanks:	365136; 365156; 365176; 365196; 365816; 365836; 365856; 365876; 365896; 365916; 365936; 365956

DEPTH (m)	AZI (Orig)	DIP	AZ (+26 Corr)	DIP (+ 27 Corr)
106.67	334.9	-48.9	0.9	1.9
185.92	335.9	-47.8	1.9	2.9
274.31	339.0	-46.0	5.0	6.0

ASSAY INTERCEPTS

FROM:	TO:	INT:	Au (g/t)	SAMPLE QUALITY:

COMMENTS: (Ground conditions, fracture zones, water flows, drilling problems)

DRILL LOG LEGEND P1	DATE: September 1-8, 2005 PAGE 1 of 12		
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
-1	0-8.53			CASING - no recovery						
10	8.53 - 274.62	8.53	15.24	GND. Unalt'd except minor oxidation and selvages around few qtz veins. Recovery is poor.	2	1				
10		15.24	21.34	Fine-grained GND; colour is greyish-beige (dry). Oxidation is pervasive.	4	1				
10		21.34	22.68	GND, all stained orange-brown except 2 small 'blue' sections of un-limonized GND, 4cm and 2cm wide. Even qtz in veins is orangey brown. Crumbly gravel texture toward end of sample.	4			1		
10		22.68	30.00	Very crumbly and broken up. Completely limonite-covered, even in otherwise unalt'd GND. Pieces up to 20cm long, but no full-diameter core. Very little clay (<5%), but very gravely to coarse sand-texture.	5	1			3	
10		30.00	34.27	Competent but weak GND. Moderately limonized and carbonitized. Veins and fractures are highly limonized with ox'd selvages. GND texture is normal - med. grained.	3				2	
10		34.27	38.40	Very crumbly, broken, limonized GND. No complete-diameter core. 60% reduced to sand and <1cm chunks of GND and qtz eyes.	4	1		1	1	
10		38.40	50.05	Competent, slightly limonized, med-grained GND. Veins are very thin, <1cm, @~30° to CA, with ox'd Fe-minerals to orange-red within veins. One different set in one interval are all ~1cm thick and appear more as silicified zones (minor bt within is disseminated). Minor hematite in veins as well (ox'd purple-black).	1	1			1	
10		50.05	57.69	Very fine-grained, silicious GND. Pale grey and uniform to ~55m. Few veins. 1cm qtz vein at 55m has slightly more silicified-than-surrounding selvage. Nearby carbonate/limonite vein has intensely orange-brown selvage, uniform for 20cm surrounding. No mineralization. Uniform ox'd orangey brown to end of section	4				2	
10		57.69	68.58	Med-grained GND with minor to moderate limonite staining; some patches of 'blue' GND ~3-5cm in diameter	2			1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: ohl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL: Sulphides								Oxidation				Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	0.5	0.5	70		2.0	cb	2	3									3.0				B365128	8.53	9.14	0.035			VA05082983	0.61
1	1	0.5	0.5	70		2.0	cb	2	3									3.0				B365129	8.53	9.14	0.037	PD/CA		VA05082983	0.61
																						B365130	STANDARD 6F		2.760	6F		VA05082983	
																						B365131	9.14	10.67	0.020			VA05082983	1.53
																						B365132	10.67	12.19	0.037			VA05082983	1.52
																						B365133	12.19	13.72	0.016			VA05082983	1.53
																						B365134	13.72	15.24	0.056			VA05082983	1.52
																						B365135	15.24	16.76	0.025			VA05082983	1.52
																						B365136	BLANK		<0.005			VA05082983	
																						B365137	16.76	18.29	0.036			VA05082983	1.53
																						B364138	18.29	19.81	0.065			VA05082983	1.52
6	1	1.5	3.5	40	60					0.1							0.1	2.0				B365139	19.81	21.34	0.137			VA05082983	1.53
2	1	1.5	2.0	50		4.0	q	5	4									3.0				B365140	21.34	22.68	0.373			VA05082983	1.34
																						B365141	22.68	23.20	0.052			VA05082983	0.52
																						B365142	22.68	23.20	0.049	DUP		VA05082983	0.52
1	1	0.5	0.5	40		1.0	cb	4	3													B365143	23.20	24.38	0.033			VA05082983	1.18
																						B365144	24.38	25.91	0.033			VA05082983	1.53
2	1	0.6	1.0	40		1.0	q	2	2									1.0				B365145	25.91	27.43	0.437			VA05082983	1.52
1	1	0.3	0.3	40		0.5	q	2	2									2.0				B365146	27.43	28.96	0.047			VA05082983	1.53
																						B365147	28.96	30.00	0.104			VA05082983	1.04
																						B365148	30.00	30.48	0.136			VA05082983	0.48
																						B365149	30.00	30.48	0.142	PD/CA		VA05082983	0.48
																						B365150	STANDARD 3C		0.088	3C		VA05082983	
2	1	0.4	0.8	50		1.0	q	3	3													B365151	30.48	32.00	0.084		lim. ox'n w/in vein	VA05082983	1.52
1	4	1.0	1.0	65																									
																						B365152	32.00	33.53	0.111			VA05082983	1.53
																						B365153	33.53	34.27	0.018			VA05082983	0.74
																						B365154	34.27	35.05	0.044			VA05082983	0.78
1	1	0.5	0.5	50		2.0	q/cb	4	2													B365155	35.05	36.58	0.080			VA05082983	1.53
																						B365156	BLANK		<0.005			VA05082983	
																						B365157	36.58	37.40	0.021			VA05082983	0.82
																						B365158	37.40	38.40	0.025			VA05082983	1.00
2	1	0.4	0.8	5	40	1.0	q/cb	4	3									20.0				B365159	38.40	39.42	0.024			VA05082983	1.02
2	1	0.5	0.8	40		1.0	q/cb	4	2									3.0				B365160	39.62	41.15	0.056			VA05082983	1.53
5	1	1.0	5.0	110	120	1.0	q	2	1											2.0									
2	1	0.3	0.6	30		0.5	q/cb	3	3									5.0				B365161	41.15	42.67	0.045			VA05082983	1.52
2	1	0.3	0.6	30		0.5	q/cb	3	3									5.0				B365162	41.15	42.67	0.015	DUP		VA05082983	1.52
2	1	0.4	0.7	30		2.0	q/s	2	4									30.0				B365163	42.67	44.20	0.312			VA05082983	1.53
2	1	0.7	1.2	0	35	1.0	q	4	3								2.0	10.0				B365164	44.20	45.72	0.025		grey qtz, moly	VA05082983	1.52
3	1	1.0	2.3	30		2.0	q/cb	4	3									3.0		3.0		B365165	45.72	47.24	0.041			VA05082983	1.52
1	1	0.4	0.4	35		4.0	q/s/cb	4	4								5.0	5.0				B365166	47.24	48.77	0.015		moly	VA05082983	1.53
5	1	0.6	3.0	30	45	4.0	q/cb	4	4									3.0				B365167	48.77	50.05	0.219			VA05082983	1.28
4	1	0.6	1.2	50	30	4.0	q/cb	5	2									5.0				B365168	50.05	50.80	0.714			VA05082983	0.75
4	1	0.6	1.2	50	30	4.0	q/cb	5	2									5.0				B365169	50.05	50.80	1.315	PD/CA		VA05082983	0.75
																						B365170	STANDARD 5E		1.470	5E		VA05082983	
2	1	0.6	1.0	30		3.0	q/cb	4	4													B365171	50.80	51.82	0.211			VA05082983	1.02
																						B365172	51.82	53.34	0.053			VA05082983	1.52
																						B365173	53.34	54.86	0.030			VA05082983	1.52
2	1	1.0	1.4	50		10.0	q	1	5									1.0				B365174	54.86	56.39	0.302			VA05082983	1.53
1	4	0.4	0.4	30		20.0	cb/lim	5	5																				
4	1	1.2	3.0	60					5									10.0				B365175	56.39	57.69	0.335			VA05082983	1.30
1	3	2.0	2.0	60		6.0	cb	5	5								0.1	15.0											
							lim	4														B365176	BLANK		<0.005			VA05082983	
4	1	0.8	2.3	50		2.0	cb/q	4	5								2.0	5.0				B365177	57.69	58.71	0.068			VA05082983	1.02

DRILL LOG LEGEND P1	DATE: September 1-8, 2005	PAGE 3 of 12	
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		68.58	80.50	Moderately ox'd GND; oxidation especially concentrated around veins and fracture infills (limonite). Competent core, regular breakage at 40° and 135° to CA. 'Other' sulphide noted throughout last section, and occurring more massively here - few veins contain >5% of it. Silver, submetallic lustre to dull grey; appears massive or flakey (micaceous), soft (2-3).	3	1			1	
10		80.50	89.92	Oxidation moderate to strong - thick crumbly to flattened (carb-rich) limonite covers most faces and can also be seen within GND matrix. Qtz veins have poor mineralization and contain only brown-black oxidation products. Fresh py (trace) seen in one vein. Recovery is good.	4	1			3	
10		89.92	92.96	Unalt'd, competent medium-grained GND with minor oxidation in 'selvages' surrounding limonitic fracture infills. This is the largest section of 'blue' GND in hole down to this point. Good mineralization within qtz veins at 20-40° to CA.	1				1	
10		92.96	98.89	Limonite returns pervasively. Rock broken into <10cm pieces to 97.4m. Recovery poor from 94.49 to 96.01m. Few 'blue' patches ~5cm in diameter at 98.5m - irregular boundaries due to lim. stained selvages around fractures.	4				2	
10		98.89	105.16	Even more limonite here. Opaque and uniform around veins. GND texture 20% erased into medium orange brown.	4	1			1	
10		105.16	117.35	Pervasively limonite-stained GND. Brown. Weak rock. Broken along parallel to CA (length-wise to core), and at 90° to CA, regularly. As well, fractures at random angles in between 0 and 90°. Gouge material (brecciated GND in clay to fine sand texture) for 15cm at 109.50m. Other evidence of motion in truncated veins (no direction avail.) along fracture. Sericitic alteration in wide selvages around lim-stained qtz/carb veins and totally oxidized sulphide veins. More gouge at 115.95 to 116.20m. Where selvages are not noted, they are not visible due to pervasive oxidation through section.	4	2			2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: ehl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL													Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides									Oxidation											
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
1	1	2.0	2.0	50		2.0	cb/q	4	3	0.1							0.1	6.0				B365178	58.71	59.44	**0.137**			VA05082983	0.73
3	1	0.5	1.1	40		2.0	cb/q	4	3								0.1	4.0				B365179	59.44	60.96	**0.023**			VA05082983	1.52
2	3	1.0	1.3	30		4.0	cb/q	4	4																				
							lim	5																					
3	1	1.0	2.2	40		2.0	q/cb	4	3								0.1	2.0				B365180	60.96	62.48	**0.268**			VA05082983	1.52
							lim																						
3	1	1.0	3.0	30	50	3.0	q	3	3									2.0				B365181	62.48	64.01	**0.281**			VA05082983	1.53
1	6	1.0	1.0	50		4.0	q/cb	2	4									100.0											
1	6	1.0	1.0	50		4.0	q/cb	2	4									100.0				B365182	62.48	64.01	**0.808**	DUP		VA05082983	1.53
2	1	1.0	1.5	50		2.0	cb	1	4									2.0				B365183	64.01	65.53	**0.050**			VA05082983	1.52
3	1	1.0	2.0	40		2.0	q/cb	3	3									6.0				B365184	65.53	67.06	**0.107**			VA05082983	1.53
3	1	1.0	2.0	5	60	2.0	q/cb	3	3									12.0				B365185	67.06	68.58	**1.410**			VA05082983	1.52
2	3	0.3	0.6	45		1.0	q/s	3	1									1.0				B365186	68.58	70.10	**0.029**			VA05082983	1.52
2	3	0.3	0.5	30		1.0	cb/q	3	1								5.0					B365187	70.10	71.63	**0.033**			VA05082983	1.53
5	1	1.0	4.5	30	50	2.0	cb/q	3	3									2.0				B365188	71.63	73.15	**0.152**			VA05082983	1.52
5	1	1.0	4.5	30	50	2.0	cb/q	3	3									2.0				B365189	71.63	73.15	**0.113**	PD/CA		VA05082983	1.52
																						B365190	STANDARD 4D		**0.435**	4D		VA05082983	
4	1	1.2	2.4	40	65	2.0	q/cb	3	3								1.0	2.0				B365191	73.15	74.68	**0.270**			VA05082983	1.53
1	1	1.1	1.1	25									2.0																
2	1	1.0	2.0	45		2.0	q	4	4		2.0	1.0	1.0									B365192	74.68	76.20	**0.203**			VA05082983	1.52
							cb	1																					
5	1	0.8	4.8	40	55	2.0	cb/q	3	1	0.1								8.0		0.1		B365193	76.20	77.72	**0.154**			VA05082983	1.52
3	1	4.0	6.0	45	60	4.0	cb/q	5	3									10.0		10.0		B365194	77.72	78.75	**0.156**			VA05082983	1.03
2	6	0.3	0.5	30	50	6.0	q/s/cb	4	5																				
1	1	0.6	0.6	10		2.0	q	4	4		10.0		5.0			0.1						B365195	78.75	79.25	**0.801**			VA05082983	0.50
																						B365196	BLANK		**<0.005**			VA05082983	
7	1	1.0	0.8	40		2.0	q	2	3	0.1	4.0		3.0			0.1		4.0				B365197	79.25	80.50	**0.311**			VA05082983	1.25
3	1	1.0	2.0	30		2.0	q/cb	5	2									4.0		1.0		B365198	80.50	81.19	**4.360**			VA05082983	0.69
3	1	1.0	3.0	55		2.0	q/cb	3	2	0.1								4.0				B365199	81.19	82.30	**0.314**			VA05082983	1.11
2	3	1.2	1.5	45		1.0	q/cb	1	2													B365200	82.30	83.82	**0.131**		NEW SAMPLE SERIES	VA05082983	1.52
3	1	2.0	3.5	55	30	0.5	q	3	3									10.0				B365801	83.82	85.34	**0.393**			VA05082983	1.52
3	1	2.0	3.5	55	30	0.5	q	3	3									10.0				B365802	83.82	85.34	**0.199**	DUP		VA05082983	1.52
5	1	1.0	4.0	50		2.0	q/s	3	2								0.1	3.0				B365803	85.34	86.87	**0.103**			VA05082983	1.53
3	1	1.0	1.6	50	60	2.0	q/cb	3	3								0.1	3.0				B365804	86.87	88.39	**0.178**			VA05082983	1.52
4	1	3.0	6.0	40		2.0	q/cb	4	3								0.1	5.0		1.0		B365805	88.39	89.92	**0.529**			VA05082983	1.53
3	4	0.5	1.3	15		1.0	cb/lim	3	5																				
5	1	0.4	1.7	40	45	1.0	q	3	1		5.0	1.0	2.0					1.0				B365806	89.92	91.44	**0.075**			VA05082983	1.52
4	1	3.0	5.5	40	20	2.0	q/cb	3	3		2.0						1.0	2.0		2.0		B365807	91.44	92.96	**0.077**			VA05082983	1.52
2	1	0.6	1.2	40	5	0.5	q	3	3									0.1				B365808	92.96	94.49	**0.057**			VA05082983	1.53
2	1	0.6	1.2	40	5	0.5	q	3	3									0.1				B365809	92.96	94.49	**0.052**	PD/CA		VA05082983	1.53
																						B365810	STANDARD 7G		**4.330**	7G		VA05082983	
1	1	1.2	1.2	22		1.0	q	3	2				0.1				2.0	5.0				B365811	94.49	96.01	**0.053**			VA05082983	1.52
2	1	1.0	1.5	5		2.0	q/cb	3	1								1.0	1.0		0.1		B365812	96.01	97.54	**0.067**			VA05082983	1.53
4	1	1.0	3.0	20	45	1.0	q	2	4									4.0		0.1		B365813	97.54	98.89	**0.220**			VA05082983	1.35
																						B365814	98.89	100.06	**1.195**			VA05082983	1.17
2	1	0.6	0.9	30		3.0	q/cb	2	5				5.0					0.1				B365815	100.06	100.58	**0.131**			VA05082983	0.52
																						B365816	BLANK		**<0.005**			VA05082983	
7	1	1.0	5.5	40	130	1.0	q/cb	3	3									3.0				B365817	100.58	102.11	**0.885**			VA05082983	1.53
3	4	0.1	0.3	40		2.0	cb	3	1													B365818	102.11	103.63	**0.108**			VA05082983	1.52
1	1	1.0	1.0	20		1.0	q	1	3		0.1	0.1	2.0					1.0											
3	1	1.0	2.5	20			q/cb	3	4									1.0				B365819	103.63	105.16	**0.035**			VA05082983	1.53
2	1	0.3	0.6	1		2.0	lim	5	5									1.0				B365820	105.16	106.68	**2.760**			VA05082983	1.52

DRILL LOG LEGEND P1	DATE: September 1-8, 2005 PAGE 5 of 12		
DRILL HOLE # : DG05-309C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered	**Carbonate** 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		117.35	121.92	GND texture returns to visibility, beneath limonite colouration, still pervasive.	3				1	
10		121.92	127.27	Back to very limonite-rich rock. 75% is opaque, brown and uniform with virtually no sign of GND texture. Sericite dominates the outer edges of these limonitic zones, up to a few cm wide. Coarse carbonate grains are also seen with textured GND zones.	4	2			2	
10		127.27	140.21	Less stained GND. Clear GND separated by selvages (lim around veins and fractures, little throughout GND matrix. Veins and veinlets are easily distinguished but most appear lim-stained and rearranged, i.e. bent or sheared. Only one carbonate vein is pristine white and un-moved. Limonite is carb-rich.	3			1	2	
10		140.32	158.50	GND with zones of variable lim-staining (oxidation) and carbonate. To 143.25m, surrounding bent, low-angle qtz veins is opaque light brown alteration in GND, to greenish grey GND with 2-4mm coarse grains of lim-stained carbonate. From 143.25 to 145.0m is 80% unalt'd, 'blue' GND. 20% is qtz veins w/ moderate mineralization and small qtz selvages, as well as a few thin carbonate/lim veinlets with relatively wide selvages. These vein types continue throughout section, with variable frequency, but usually 2-4 per metre. Zone of brecciated, sandy, lim-covered pebbles from 151.2 to 151.6m, with some loss of recovery here. Large selvages around fractures: 4cm+ 'chunky' carbonate within lim as above. Outer selvage (2cm+) is moderately silicified and has minor sericite. At 156.75 to 157.75m, evidence of shear appears - foliation development (at ≥50° to CA) and increase in clay minerals. GND's	3	1		1	2	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Interval					
										Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
3	1	0.2	0.6	20														2.0				B365821	106.68	108.20	**1.665**			VA05082983	1.52
3	1	0.2	0.6	20														2.0				B365822	106.68	108.20	**3.400**	DUP		VA05082983	1.52
																						B365823	108.20	109.73	**0.118**			VA05082983	1.53
1	1	1.0	1.0	45														4.0				B365824	109.73	111.25	**0.046**			VA05082983	1.52
3	1	1.0	2.1	50														3.0				B365825	111.25	112.77	**0.043**			VA05082983	1.52
1	1	0.5	0.5	40														2.0				B365826	112.77	114.30	**0.134**			VA05082983	1.53
1	6	0.2	0.2	45		8.0	q/s/cb	5	2									100.0											
2	1	0.6	1.0	40	55													6.0				B365827	114.30	115.82	**0.049**			VA05085049	1.52
1	3	1.0	1.0	40		20.0	q/s	4	5																				
4	1	1.0	3.0	45													0.1	1.0				B365828	115.82	117.35	**0.197**			VA05085049	1.53
4	1	1.0	3.0	45													0.1	1.0				B365829	115.82	117.35	**0.207**	PD/CA		VA05085049	1.53
																						B365830	STANDARD 3C		**0.092**	3C		VA05085049	
2	1	1.0	1.6	40	50	2.0	q	3	3		0.1	0.1	2.0				1.0	3.0				B365831	117.35	117.95	**0.207**			VA05085049	0.60
3	1	0.5	1.5	45														8.0				B365832	117.95	119.03	**0.108**			VA05085049	1.08
1	1	1.0	1.0	50									0.1					2.0				B365833	119.03	120.40	**0.411**			VA05085049	1.37
3	1	0.5	1.5	45	20													2.0				B365834	120.40	121.92	**0.233**			VA05085049	1.52
3	1	0.5	1.5	35	20	4.0	cb/q	3	5	1.0								6.0				B365835	121.92	123.44	**0.350**			VA05085049	1.52
																						B365836	BLANK		**<0.005**			VA05085049	
3	1	1.0	1.8	40		4.0	cb/q	4	4				0.1		0.1			4.0				B365837	123.44	124.97	**0.734**			VA05085049	1.53
4	1	1.0	3.5	25	40	8.0	cb/s	4	4									1.0				B365838	124.97	126.49	**0.201**			VA05085049	1.52
2	1	1.0	2.0	40	30	3.0	cb/s	3	3				0.1		1.0			3.0				B365839	126.49	127.27	**0.347**			VA05085049	0.78
2	4	1.5	2.0	20	35	12.0	cb	3	5																				
3	1	1.0	3.0	20									1.0		1.0			1.0				B365840	127.27	128.68	**0.054**			VA05085049	1.41
1	4	0.6	0.6	35		6.0	cb/s	3	4									0.1											
2	1	1.0	2.0	40	20	3.0	q/cb	3	2						2.0			1.0				B365841	128.68	129.54	**0.205**			VA05085049	0.86
2	1	1.0	2.0	40	20	3.0	q/cb	3	2						2.0			1.0				B365842	128.68	129.54	**1.475**	DUP		VA05085049	0.86
4	1	1.0	3.6	45		2.0	cb/q	2	3						1.0			1.0				B365843	129.54	131.07	**0.293**			VA05085049	1.53
1	4	0.5	0.5	25		2.0	cb/q	3	4																				
3	1	2.0	4.0	30		1.0	q	2										1.0				B365844	131.07	132.59	**0.060**			VA05085049	1.52
2	1	0.5	1.0	35		2.0	q/cb/s	2	2									2.0				B365845	132.59	134.12	**0.051**			VA05085049	1.53
5	1	0.5	2.5	40	25	3.0	q/cb/s	3	2		2.0				4.0			2.0				B365846	134.12	135.64	**0.134**			VA05085049	1.52
4	1	1.1	3.5	30		2.0	q/s/cb	2	3				2.0		3.0							B365847	135.64	137.16	**0.181**			VA05085049	1.52
4	1	1.0	3.5	45		2.0	q/s/cb	3	1		2.0				1.0							B365848	137.16	138.68	**5.460**			VA05085049	1.52
4	1	1.0	3.5	45		2.0	q/s/cb	3	1		2.0				1.0							B365849	137.16	138.68	**5.160**	PD/CA		VA05085049	1.52
																						B365850	STANDARD 7G		**4.570**	7G		VA05085049	
7	1	1.0	6.0	30	20	2.0	q	4	1		3.0		1.0					2.0				B365851	138.68	140.21	**1.135**			VA05085049	1.53
							cb/s	1																					
6	1	1.0	5.2	40	160	4.0	q	4	2													B365852	140.21	141.73	**0.723**			VA05085049	1.52
1	4	0.5	0.5	25																									
1	4	0.4	0.4	160														10.0											
2	1	2.0	3.0	30		2.0	q	3	1		2.0		1.0									B365853	141.73	143.25	**0.423**			VA05085049	1.52
3	1	1.0	3.0	40		1.0	q	2	1		1.0		0.1									B365854	143.25	144.78	**0.163**			VA05085049	1.53
3	1	0.5	1.5	40		1.0	q	3	1		1.0							2.0				B365855	144.78	146.31	**0.589**			VA05085049	1.53
1	4	0.3	0.3	50		8.0	cb/s/q	3	2																				
																						B365856	BLANK		**<0.005**			VA05085049	
3	1	0.5	1.5	45		2.0	q	2	4		1.0							1.0				B365857	146.31	147.83	**0.836**			VA05085049	1.52
4	1	0.5	2.0	50	20	1.0	q/s	3	1		1.0						1.0	0.1				B365858	147.83	149.35	**0.163**			VA05085049	1.52
3	4	0.2	0.6	40		12.0	cb/s	4	3									1.0											
3	1	1.0	2.6	40	20	1.0	q	3										2.0				B365859	149.35	150.88	**0.381**			VA05085049	1.53
2	1	0.5	1.0	45	20	0.5	q	3	1									4.0		2.0		B365860	150.88	152.40	**0.063**			VA05085049	1.52
																						B365861	152.40	153.92	**0.726**			VA05085049	1.52

DRILL LOG LEGEND P1	DATE: September 1-8, 2005 PAGE 7 of 12	
DRILL HOLE # : DG05-309C	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41; BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		158.50	159.42	Fault zone's focus. All fine-grained gouge except general line of (usually) broken qtz veins. Clay-rich (30%), and colourful - yellow, orangey brown, blue green, for 40cm. Granular texture reappears at 159.2m.	4	3		3	3	
10		159.42	163.07	GND texture here - ~20% unox'd, unalt'd, weak from numerous lim fract in-fills. Qtz veins still not complete.	3				1	
10		163.07	164.59	Carb-clay veins at 25° and 135° to CA through sericitic/ opaque lim'd brown rock, very weak and crumbly.	4	3		3	5	
10		164.59	181.36	Unalt'd, competent GND except surrounding qtz, qtz/carb and carb veins. Mineralization is good. VG seen associated with pyrite, also significant aspy and po. Minor limonite and carbonate. Sericite appears in selvages more strongly toward middle-end of section. Scorodite seen (bright blue-green) in one vein and selvage.	2	2			1	
10		181.36	185.94	Sericitic alteration pervasive here. Limonite and oxidation confined to veinlets and minor within selvages, minor through matrix, last metre of section. Good mineralization. One sulphide vein at 182.4m contains 1-2mm euhedral pyrite, ox'd and un-ox'd	1	1			1	
10		185.94	202.69	From 185.94 to 191.27m, rock is unalt'd GND except selvages surrounding qtz veins ± carbonate. At 191.27m, zone of extreme alt'n begins with massive sulphide veins to 192.50m. After this alt'd section, rock is competent and unalt'd except silicified and ser'd selvages surrounding qtz veins. One carb/ser-covered fracture breaks core in half at 0° to CA from 194.5 to 195.0m. No evidence of motion here.	1					

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar., 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides										Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
																						B365862	152.40	153.92	0.199	DUP		VA05085049	1.52
3	1	1.0	2.8	40		2.0	q/s	2										4.0				B365863	153.92	155.45	0.271			VA05085049	1.53
2	3	1.0	1.5	60	30	6.0	q/cb	3	4									0.1											
							s	2																					
2	1	1.0	1.5	40		1.0	q	4	2									1.0				B365864	155.45	156.97	0.926			VA05085049	1.52
2	4	2.0	3.0	70		2.0	cb/s	4	2									4.0											
1	1	1.2	1.2	10							2.0						1.0					B365865	156.97	158.50	0.063			VA05085049	1.53
4	1	1.0	3.0	20														1.0				B365866	158.50	159.42	0.458			VA05085049	0.92
3	1	1.0	2.5	50							0.1									1.0		B365867	159.42	160.02	0.037			VA05085049	0.60
1	1	0.4	0.4	60		0.5	cb	2	2									0.1				B365868	160.02	161.55	0.080			VA05085049	1.53
1	1	0.4	0.4	60		0.5	cb	2	2									0.1				B365869	160.02	161.55	0.098	PD/CA		VA05085049	1.53
																						B365870	STANDARD 1A		0.880	1A		VA05085049	
2	1	1.0	1.5	50		2.0	q/cb	5	2		0.1									2.0		B365871	161.55	163.07	0.245			VA05085049	1.52
2	1	1.0	2.0	50	35																	B365872	163.07	164.59	0.099			VA05085049	1.52
3	4	1.0	3.0	45	150		s/cb	5	4									0.1											
4	1	3.0	7.0	45		2.0	q/cb	4	3	3.0	2.0							2.0				B365873	164.59	166.12	1.040			VA05085049	1.53
3	1	1.0	2.5	40		0.5	q	3	1		2.0							0.1				B365874	166.12	167.65	0.111			VA05085049	1.53
							s	1																					
5	1	4.0	8.0	40		1.0	q/cb	3		5.0			2.0					5.0				B365875	167.65	169.16	1.770			VA05085049	1.51
3	3	1.2	2.4	50		30.0	cb/s	4	1																				
																						B365876	BLANK		<0.005			VA05085049	
5	1	2.0	6.0	30	50	1.0	2	q											8.0			B365877	169.16	170.68	0.949			VA05085049	1.52
3	4	1.0	2.0	60		10.0	cb/s	3	1																				
6	1	5.0	9.0	35	60	4.0	q	3	1	5.0						1.0						B365878	170.68	172.21	5.360			VA05085049	1.53
1	3	0.5	0.5	35		1.0	q/cb	3	2									4.0											
4	1	4.0	6.0	50		2.0	q	3		3.0	5.0	0.1	0.1					2.0				B365879	172.21	173.74	0.651			VA05085049	1.53
							cb/s	2	1																				
6	1	1.0	5.0	45		2.0	q/s	3	1		4.0		2.0			0.1		2.0				B365880	173.74	175.26	12.650			VA05085049	1.52
							cb	1																					
6	1	1.0	4.5	35	40	2.0	q/s	3	1		2.0		0.1					5.0				B365881	175.26	176.79	0.703			VA05085049	1.53
6	1	1.0	4.5	35	40	2.0	q/s	3	1		2.0		0.1					5.0				B365882	175.26	176.79	0.662	DUP		VA05085049	1.53
5	1	6.0	10.5	50		2.0	q/cb/s	3	1	3.0								1.0				B365883	176.79	178.31	1.255			VA05085049	1.52
4	1	3.0	6.5	40	60	6.0	q/s	3	1		0.1		0.1					4.0				B365884	178.31	179.83	0.967			VA05085049	1.52
6	1	2.5	7.5	30	60	4.0	q/s	3	1		1.0		0.1				2.0					B365885	179.83	181.36	1.410			VA05085049	1.53
							cb	1																					
5	1	1.2	4.0	60		4.0	q/s	3			1.0											B365886	181.36	182.12	7.230			VA05085049	0.76
							cb	1																					
1	1	1.0	1.0	40		6.0	q/s/cb	4	1	3.0	3.0							1.0				B365887	182.12	182.88	0.783			VA05085049	0.76
1	6	6.0	6.0	40		40.0	q/cb/s	4	1	40.0	0.1							50.0											
4	1	1.2	3.5	60			s/cb	4	1	1.0	0.1					1.0		1.0				B365888	182.88	184.40	1.890			VA05085049	1.52
3	3	1.0	2.5	60	40		q/cb	4	1							2.0		3.0											
3	3	1.0	2.5	60	40		q/cb	4	1							2.0		3.0				B365889	182.88	184.40	1.695	PD/CA		VA05085049	1.52
																						B365890	STANDARD 5E		1.425	5E		VA05085049	
3	1	1.0	2.7	60	40	20.0	q/s	3	2									0.1				B365891	184.40	185.94	0.554			VA05085049	1.54
							cb	1																					
3	1	1.5	2.5	35	70	1.0	q	3										0.1				B365892	185.94	187.45	0.958			VA05085049	1.51
4	1	0.5	2.0	50		6.0	q/s	4	1	8.0			0.1					4.0				B365893	187.45	188.98	0.250			VA05085049	1.53
3	1	1.0	3.0	45		2.0	cb/q/s	4			2.0	0.1	2.0							1.0		B365894	188.98	190.50	0.259			VA05085049	1.52
1	3	4.0	4.0	60		4.0	cb/s	4	1	0.1	5.0		0.1																
2	1	0.5	1.0	50		1.0	q	3	1											3.0		B365895	190.50	191.27	0.488			VA05085049	0.77
1	3	0.2	0.2	40		6.0	cb/s	3	1									5.0											
																						B365896	BLANK		<0.005			VA05085049	
2	1	1.0	1.5	70		4.0	cb/q	1	1	10.0								20.0				B365897	191.27	192.02	0.156			VA05085049	0.75
3	6	1.5	3.5	40			s/cb	4	2	60.0			2.0					38.0											
1	3	0.4	0.4	50														5.0											
6	1	1.0	4.0	50	70	2.0	q/s	3	1	0.1								4.0				B365898	192.02	193.55	0.372			VA05085049	1.53

DRILL LOG LEGEND P1	DATE: September 1-8, 2005 PAGE 9 of 12	
DRILL HOLE # : **DG05-309C**	**FeOx** 0 = Unoxidized 5 = Intensely Ox'd	**Ser, Chl, etc** 0 = Unaltered 5 = Intensely Altered
		Carbonate 0 = No Effervescence 5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41 BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		202.69	207.27	60% strongly alt'd with carb and ser. All alt'n associated with qtz, qtz/carb, and carb veins. Minor limonite on randomly-oriented fractures and within selvages. One 8cm zone of carb-rich (+ser) clay at 205.86m, associated with black clay veinlet (ox'd py?).	1	3		1	2	
10		207.27	225.54	Sheeted qtz veins with small qtz/ser/carb selvages. Mineralization is variable from vein to vein - some have up to 10% sulphides (including scor, bt, and ox'd), while others have <1%. Selvages increase in intensity and sericitic and carbonitic alteration and size toward middle of section.	1	2			2	
10		225.54	262.13	Competent, unalt'd GND with excellent recovery. Sheeted qtz veins (grey qtz). Very little breakage - common 5 foot lengths of core. Breaks are at zones of weakness (carb-rich veins, concentrations of veins, or within selvage material). Breaks are few. Selvage material blends into surrounding medium-to-coarse grained GND texture. Scor. conc at boundaries to veins; po exposed on rough breakage faces - pale silvery bronze - metallic lustre. Appears 'flattened' over qtz, etc). Slight carb increase from 247.40 to 248.60m and loss of recovery; weakness: slickensides in po - metallic, mod'ly ox'd into carb clay which is also slickensided - no vein assoc on face at 50° to CA. Nearby vein at 50°; Selvages increase in intensity with increased sulphide content in vein and at margins in selvages; Carbonate-sand and brecciated GND contacts competent GND @ 30° to CA @ 262.0m, crumbly and weak foliation for ~1m; Fractures have no selvages but fracture faces show a thin film of clay/carb and one face has ~80% coverage of po and minor aspy with no associated vein; Fresh and subhedral		1			1	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2006

LOGGED BY: M. Stone

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar , 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS						Selvages				% of VEIN & DISSEMINATED MATERIAL														Sample Number	Interval		Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
										Sulphides									Oxidation												
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other		From	To					
							cb	1																						
4	1	1.0	4.0	55	35	1.0	q	3			1.0							1.0				B365899	193.55	195.08	**1.940**			VA05085049	1.53
1	1	1.0	1.0	60		6.0	q/cb	5		1.0	2.0							1.0		2.0										
2	3	1.0	2.0	60		10.0	q/cb/s	5										1.0												
5	1	1.0	4.0	40		3.0	q/s	4			4.0		1.0				0.1	0.1				B365900	195.08	196.60	**1.360**			VA05085049	1.52
5	1	2.0	5.5	55	40	2.0	q/s	3			5.0		1.0					4.0				B365901	196.60	198.11	**0.279**			VA05085049	1.51
5	1	2.0	5.5	55	40	2.0	q/s	3			5.0		1.0					4.0				B365902	196.60	198.11	**0.880**	DUP		VA05085049	1.51
2	1	1.0	2.0	70														2.0				B365903	198.11	199.64	**0.747**			VA05085049	1.53
4	1	1.0	5.0	65		1.0	q	3	2		2.0				1.0			0.1				B365904	199.64	201.17	**0.090**			VA05085049	1.53
1	4	1.0	1.0	50		20.0	q/s	4	2									0.1												
							cb	2																						
7	1	1.0	5.5	40	55	4.0	q	4	1		4.0							1.0		0.1		B365905	201.17	202.69	**0.108**			VA05085049	1.52
							s/cb	1																						
4	1	2.0	5.0	50	80	20.0	q/s	4			2.0		0.1					1.0				B365906	202.69	204.21	**0.877**			VA05085049	1.52
2	3	1.0	2.0	30	60	10.0	cb/s	5	1									4.0												
4	1	1.0	3.0	50	60					1.0								0.1				B365907	204.21	205.74	**0.257**			VA05085049	1.53
2	3	1.0	2.0	30	70													5.0												
5	1	1.2	3.5	60	20	40.0	q/s	4		0.1								2.0				B365908	205.74	207.27	**0.295**			VA05085049	1.53
							cb	1	1																					
5	1	1.2	3.5	60	20	40.0	q/s	4		0.1								2.0				B365909	205.74	207.27	**0.288**	PD/CA		VA05085049	1.53
																						B365910	STANDARD 4D		**0.445**	4D		VA05085049	
6	1	4.0	12.0	50	30	3.0	q	2		0.1	0.1				2.0		1.0	2.0	1.0			B365911	207.27	208.74	**1.805**			VA05085049	1.47
5	1	1.0	4.5	40	60	2.0	q/s	3	1		7.0		0.1									B365912	208.74	210.30	**1.150**			VA05085049	1.56
3	1	0.6	1.4	40	60	1.0	q/s	3	1		2.0											B365913	210.30	211.84	**0.380**			VA05085049	1.54
9	1	1.3	6.5	50		2.0	q/s/cb	4	1	0.1	3.0		0.1						1.0	0.1		B365914	211.84	213.36	**0.354**			VA05085049	1.52
7	1	1.0	4.5	50		2.0	q/cb	4	1		1.0		1.0					1.0	2.0			B365915	213.36	214.88	**0.950**			VA05085049	1.52
																						B365916	BLANK		**<0.005**			VA05085049	
2	4	1.0	1.5	60		20.0	cb/s	3		0.1	0.1							3.0				B365917	214.88	216.40	**0.425**			VA05085049	1.52
4	1	1.5	4.0	40	50	3.0	q/s	4										5.0												
							cb	1																						
8	1	1.0	7.0	30	60	4.0	q/s	3			3.0							0.1				B365918	216.40	217.95	**0.466**			VA05085049	1.55
5	1	4.0	7.5	60	25	20.0	q/cb/s	5			5.0		1.0				0.1	0.1	2.0	1.0		B365919	217.95	219.45	**0.628**			VA05085049	1.50
5	1	1.0	4.0	60	45	30.0	q/s/cb	5	1		2.0				0.1			0.1	2.0	2.0		B365920	219.45	220.98	**1.330**			VA05085049	1.53
3	1	2.0	4.0	40		4.0	q	4	1	2.0								0.1				B365921	220.98	222.50	**1.140**			VA05085049	1.52
3	3	0.7	2.0	30		10.0	cb/s	5	1									2.0												
3	1	2.0	4.0	40		4.0	q	4	1	2.0								0.1				B365922	220.98	222.50	**0.660**	DUP		VA05085049	1.52
3	3	0.7	2.0	30		10.0	cb/s	5	1									2.0												
5	1	1.0	3.5	45		1.0	q	3														B365923	222.50	224.03	**0.455**			VA05085049	1.53
							s	1																						
3	3	1.0	2.5	50	30	8.0	cb/s	4			4.0						0.1	3.0												
7	1	1.2	8.0	45		2.0	q/s	3			1.0							0.1	2.0	2.0		B365924	224.03	225.54	**0.159**			VA05085049	1.51
							cb	2	2																					
5	1	1.0	3.0	60		20.0	cb/s	4	3		1.0							1.0				B365925	225.54	227.08	**0.176**			VA05085049	1.54
4	1	2.5	5.0	50		2.0	q	4	1		3.0							2.0	1.0	3.0		B365926	227.08	228.60	**0.219**			VA05085049	1.52
5	1	1.0	4.0	50		2.0	q	4			4.0											B365927	228.60	230.12	**0.213**			VA05085049	1.52
							cb/s	1																						
6	1	1.0	6.0	40	55	6.0	q/cb/s	4			6.0	0.1	1.0					1.0	5.0			B365928	230.12	231.65	**0.185**			VA05085049	1.53
6	1	1.0	6.0	40	55	6.0	q/cb/s	4			6.0	0.1	1.0					1.0	5.0			B365929	230.12	231.65	**0.217**	PD/CA		VA05085049	1.53
																						B365930	STANDARD 7G		**4.550**	7G		VA05085049	
4	1	0.5	2.0	50		2.0	q/cb	2														B365931	231.65	233.17	**0.386**			VA05085049	1.52
							s	1																						
7	1	1.0	5.5	50		2.0	q/s	4			2.0		0.1						5.0	0.1		B365932	233.17	234.70	**0.241**			VA05085049	1.53
6	1	1.0	5.5	60		4.0	cb/s	3			3.0		1.0					3.0				B365933	234.70	236.22	**1.040**			VA05085049	1.52

DRILL LOG LEGEND - P1

DRILL HOLE # :
DG05-309C

DATE: September 1-8, 2005 PAGE 11 of 12

FeOx
0 = Unoxidized
5 = Intensely Ox'd

Ser, Chl, etc
0 = Unaltered
5 = Intensely Altered

Carbonate
0 = No Effervescence
5 = Strong Effervescence

Lith Code: -1 = No Code; OVB = 1; GND = 10; GND (fg) = 11; GNDD (dyke) = 12; QMON = 20; DIOR = 25; MGD = 30; APL = 40; FLCD = 41
BQAH = 60; BAH = 61; CHN = 65; QZZ = 70; MSED = 80; HFLS = 81; PHYL = 82; BQS = 85; QTZ = 90; FZ = 92; SZ = 93

UNIT CODE	From → To:	From:	To:	GEOLOGICAL DESCRIPTION Comments:	ROCK (Alteration) Oxide (ox)	Sericite (ser)	Chlorite (chl)	Clay (arg)	Carb (carb)	Other
10		262.13	271.28	More carb-rich GND. Breakage into <10cm lengths, random fracture orientations (see tech sheets). Still, good recovery overall. Carb concentrated in selvages further into section: @266.75 - 271.28m. Max selvages noted on next page. Last sample high carb and ser - grades into next section. Strong slickensides on low angle (~10° to CA) frac faces @270m.	1	2			2	
10		271.28	274.62	GND: Strong slickensides noted in low angle fractures continue. Increase in carb + ser alt'n to EOH - selvages often indistinguishable from one another.		2			3	

DRILL LOG LEGEND P2

Selvages
0 = No Alteration
5 = Intense Alt'n

Ox. State
0 = No Oxidized Sulphides
5 = All Sulph Oxidized

Date: September 1-8, 2005

LOGGED BY: M. Stone

PAGE 12 of 12


094876

Selvage Alteration: chl = chlorite, k = K-spar, s = sericite, q = quartz/silica, cb = carbonate, b = biotite, cc = calcite

Vein Type: 1 = quartz, 2 = quartz/K-spar, 3 = quartz/carbonate, 4 = carbonate, 5 = quartz/chlorite, 6 = sulphide +/- quartz

VEINS										% of VEIN & DISSEMINATED MATERIAL												Interval						
						Selvages				Sulphides									Oxidation										
#/meter	Type	Max. (cm)	Total (cm)	Prim Ang V1	2nd Ang V2	Max (cm)	Alteration	(0-5)	Ox. State 0-5	pyrite	pyrrhotite	chalcopyrite	arsenopyrite	bismuthite	sphalerite	visible gold	other	oxide	scordite	biotite	other	Sample Number	From	To	Au (g/T)	Type of Sample	Vein Comments	CSV	Width (m)
6	1	1.0	3.0	45	30	3.0	q/s	4			5.0		2.0						2.0	1.0		B365934	236.22	237.75	**0.568**			VA05085049	1.53
6	1	35.0	9.0	50		2.0	q	4			2.0		1.0							1.0		B365935	237.75	239.27	**0.423**			VA05085049	1.52
							cb/s	2																				
																						B365936	BLANK		**<0.005**			VA05085049	
6	1	3.0	6.0	50	35	1.0	q	4	0		2.0							1.0	5.0			B365937	239.27	240.80	**1.125**			VA05085049	1.53
8	1	0.5	4.0	50	80	4.0	q	4			0.1								5.0	1.0		B365938	240.80	242.32	**0.288**			VA05085049	1.52
8	1	1.0	5.0	60		3.0	q/s	4			1.0									2.0		B365939	242.32	243.85	**0.315**			VA05085049	1.53
5	1	2.0	4.0	50	20	4.0	q/s/cb	5	0		5.0	0.1	3.0					3.0				B365940	243.85	245.36	**0.243**			VA05085049	1.51
4	1	1.0	3.0	45		28.0	q/cb	5			10.0								5.0	1.0		B365941	245.36	246.89	**0.117**			VA05085049	1.53
4	1	1.0	3.0	45		28.0	q/cb	5			10.0								5.0	1.0		B365942	245.36	246.89	**1.080**	DUP		VA05085049	1.53
3	1	1.0	3.0	50		4.0	q/s	3	0		1.0									0.1		B365943	246.89	248.41	**0.456**			VA05085049	1.52
5	1	1.0	5.0	60		1.0	q	4	0		1.0							10.0	5.0			B365944	248.41	249.94	**0.290**			VA05085049	1.53
6	1	1.5	6.0			2.0	q	4			2.0								4.0			B365945	249.94	251.46	**0.255**			VA05085049	1.52
5	1	1.0	5.0	50		4.0	s/q	3			0.1	0.1							6.0			B365946	251.46	252.99	**0.097**			VA05085049	1.53
4	1	1.0	4.0	50		2.0	q/s	3											2.0			B365947	252.99	254.51	**0.282**			VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365948	254.51	256.03	**0.261**			VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365949	254.51	256.03	**0.493**	PD/CA		VA05085049	1.52
3	1	1.0	2.5	40							1.0								4.0	2.0		B365950	STANDARD 2B		**2.970**	2B		VA05085049	
6	1	2.0	5.0	45		6.0	cb/s	4	1		3.0	1.0							3.0			B365951	256.03	257.56	**0.169**			VA05085049	1.53
8	1	1.0	7.0	40	55	4.0	q/s	3		1.0	1.0								2.0	0.1		B365952	257.56	259.09	**1.330**			VA05085049	1.53
1	1	0.5	0.5	60		1.0	q/s	3			1.0											B365953	259.09	260.60	**0.025**			VA05085049	1.51
4	1	0.5	2.0	60		2.0	q/s	5	0									tr				B365954	260.60	262.13	**0.100**			VA05085049	1.53
3	1	1.0	3.0	40		4.0	q	3	0		3.0								1.0	2.0		B365955	262.13	263.65	**0.066**			VA05085049	1.52
																						B365956	BLANK		**<0.005**			VA05085049	
2	1	1.0	2.0	50		10.0	q/s	4			2.0						1.0					B365957	263.65	265.17	**0.124**		musc. Or moly diss. In selvage	VA05085049	1.52
3	1	1.0	3.0	45		40.0	bc/s	4		8.0								1.0				B365958	265.17	266.70	**0.119**		massive py also in veinlets w/in 1cm of qtz vein	VA05085049	1.53
2	1	1.0	2.0	65		3.0	cb/q	4			1.0		2.0					2.0	6.0			B365959	266.70	268.23	**0.062**			VA05085049	1.53
3	1	1.0	2.0	50		3.0	q/s	5			4.0							1.0				B365960	268.23	269.75	**0.063**			VA05085049	1.52
							cb	2																				
4	1	1.0	4.0	30	60	8.0	s/cb	4			2.0											B365961	269.75	271.28	**0.036**			VA05085049	1.53
4	1	1.0	4.0	30	60	8.0	s/cb	4			2.0											B365962	269.75	271.28	**0.075**	DUP		VA05085049	1.53
1	6	1.0	1.0	35		30.0	c/b	4		5.0								90.0				B365963	271.28	272.80	**0.042**		numerous carb veinlets	VA05085049	1.52
1	1	1.0	1.0	35			s/q	2																					
2	1	1.5	1.0	70		1.0	q	5		3.0										2.0		B365964	272.80	274.62	**0.139**		10%clay min (white) + carb.	VA05085049	1.82
2	6	1.0	1.5	50		40.0	cb	5										90.0											
																							EOH						

094876



APPENDIX G

ALS Chemex Assay Certificates

- Drilling -

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da[illegible]-JUN-2005
Account: STRGOL

CERTIFICATE VA05042605

Project: Dublin Gulch-1735

P.O. No.:

This report is for 113 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 1-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate


ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

094876

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291001		0.76	0.013	<0.5	7.60	381	1620	3.2	<2	2.01	<0.5	9	38	62	2.54	0.01
B291002		0.58	0.107	<0.5	7.14	452	1480	3.1	<2	1.82	<0.5	9	60	54	2.38	0.01
B291003		1.90	0.521	<0.5	7.46	691	1510	3.0	5	1.62	<0.5	7	29	62	2.23	0.01
B291004		1.48	0.024	1.3	7.60	391	1600	3.1	<2	2.07	<0.5	8	41	55	2.40	0.01
B291005		1.82	0.079	<0.5	7.40	788	1490	3.0	8	1.72	<0.5	8	28	54	2.32	0.01
B291006		0.20	0.164	<0.5	7.47	1765	1510	3.1	17	1.84	<0.5	9	48	62	2.58	0.01
B291007		1.04	0.009	<0.5	7.12	209	1500	3.1	<2	2.11	<0.5	7	28	25	2.31	<0.01
B291008		0.42	0.018	<0.5	7.42	318	1550	3.1	<2	1.73	<0.5	6	45	27	2.30	<0.01
B291009		0.04	0.018													
B291010		0.12	0.081	<0.5	7.26	117	590	2.7	<2	0.52	<0.5	60	1235	396	8.59	0.03
B291011		1.86	2.40	<0.5	7.82	358	1460	2.9	<2	1.77	<0.5	7	27	37	2.21	0.01
B291012		0.12	0.111	<0.5	7.36	996	1410	2.8	12	1.52	<0.5	9	54	50	2.36	0.01
B291013		2.94	0.133	<0.5	7.54	717	1430	3.0	9	1.18	<0.5	8	27	48	2.09	0.01
B291014		2.22	0.089	<0.5	7.45	742	1550	3.0	5	1.86	<0.5	9	43	49	2.21	0.01
B291015		4.00	0.059	<0.5	7.52	447	1600	3.0	4	2.01	<0.5	7	29	39	2.35	0.01
B291016		0.94	<0.005	<0.5	0.13	<5	20	<0.5	<2	18.85	<0.5	1	5	2	0.10	<0.01
B291017		1.60	0.019	<0.5	7.52	307	1590	3.2	2	1.94	<0.5	7	28	51	2.27	0.01
B291018		3.98	0.056	<0.5	7.73	411	1580	3.2	3	2.01	<0.5	7	48	42	2.33	0.01
B291019		4.50	0.034	<0.5	6.98	416	1500	3.0	4	1.85	<0.5	7	27	49	2.18	0.01
B291020		3.34	0.073	<0.5	7.38	437	1480	2.9	6	1.74	<0.5	8	39	55	2.20	0.01
B291021		0.40	0.060	<0.5	7.59	640	1370	3.0	20	1.52	<0.5	11	26	87	2.19	0.01
B291022		0.40	0.090	<0.5	7.20	458	1350	2.9	9	1.58	<0.5	8	47	58	2.10	0.01
B291023		3.72	0.074	<0.5	7.80	586	1410	3.3	18	2.23	<0.5	8	37	47	2.48	0.01
B291024		4.88	0.229	<0.5	7.72	506	1570	3.0	16	1.80	<0.5	8	45	82	2.40	0.01
B291025		4.14	0.049	<0.5	7.50	513	1530	3.0	4	1.80	<0.5	9	29	45	2.25	<0.01
B291026		1.80	0.106	<0.5	7.68	637	1600	3.0	10	1.96	<0.5	9	42	57	2.26	<0.01
B291027		1.58	0.072	<0.5	7.28	696	1350	2.9	4	2.19	<0.5	7	25	48	1.80	0.01
B291028		2.44	0.121	<0.5	7.44	758	1480	2.9	19	1.82	<0.5	8	37	53	2.19	0.01
B291029		0.04	0.130													
B291030		0.10	0.089	<0.5	6.66	103	560	2.5	2	0.49	<0.5	55	1095	375	7.89	0.03
B291031		0.54	0.400	<0.5	7.58	416	1490	2.8	20	1.52	<0.5	6	28	52	1.81	<0.01
B291032		3.08	0.265	<0.5	6.99	800	1220	2.5	10	1.21	<0.5	7	35	77	1.76	<0.01
B291033		4.56	0.101	<0.5	7.34	565	1560	2.9	6	2.08	<0.5	7	28	62	2.29	0.01
B291034		2.02	0.114	<0.5	7.96	390	1590	3.2	4	1.94	<0.5	8	45	48	2.33	0.01
B291035		2.40	0.069	<0.5	7.55	749	1670	3.0	6	2.18	<0.5	7	30	48	2.42	0.01
B291036		1.06	<0.005	<0.5	0.11	6	10	<0.5	<2	19.60	<0.5	<1	4	1	0.11	<0.01
B291037		2.24	0.057	<0.5	7.56	595	1480	3.2	3	2.06	<0.5	7	25	46	2.23	0.01
B291038		3.30	0.073	<0.5	7.35	648	1540	2.9	6	2.59	<0.5	8	40	45	2.37	0.01
B291039		3.96	0.416	<0.5	7.25	454	1510	2.9	11	1.94	<0.5	8	27	40	2.37	0.01
B291040		2.06	0.058	<0.5	7.59	424	1580	3.1	3	2.03	<0.5	8	38	24	2.35	0.01

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291001		3.61	0.84	250	<1	1.79	26	680	22	0.04	<5	486	0.34	43	40	52
B291002		3.45	0.83	228	<1	1.67	22	650	18	0.05	<5	443	0.31	42	20	39
B291003		3.79	0.64	202	1	1.51	19	620	20	0.01	10	388	0.30	38	50	36
B291004		3.74	0.69	225	4	1.66	22	660	17	0.01	8	437	0.32	38	30	40
B291005		3.95	0.69	217	<1	1.57	19	610	21	0.01	<5	411	0.31	38	40	42
B291006		3.76	0.77	222	<1	1.61	23	680	17	0.01	5	441	0.33	40	30	39
B291007		3.52	0.73	255	<1	1.79	21	630	18	0.02	<5	467	0.32	37	10	45
B291008		3.79	0.74	217	<1	1.71	18	650	22	0.01	<5	439	0.31	37	20	41
B291009																
B291010		2.19	0.58	389	8	0.12	497	350	148	0.02	14	52	0.24	93	30	647
B291011		3.97	0.71	192	<1	1.59	21	600	21	0.01	<5	408	0.29	33	70	34
B291012		4.07	0.71	196	1	1.50	20	590	18	0.01	7	393	0.28	34	100	35
B291013		3.83	0.54	211	2	1.22	22	640	33	0.01	15	273	0.30	37	20	85
B291014		3.85	0.76	186	3	1.64	20	620	21	0.05	<5	459	0.31	36	20	33
B291015		3.65	0.77	224	1	1.68	20	630	20	0.01	<5	462	0.31	37	40	39
B291016		0.04	11.60	146	<1	0.02	4	430	2	0.01	<5	106	<0.01	3	<10	8
B291017		3.73	0.76	180	1	1.79	21	620	21	0.01	<5	470	0.31	37	10	49
B291018		3.74	0.79	209	1	1.74	21	630	22	0.01	<5	477	0.31	37	10	49
B291019		3.54	0.71	196	1	1.65	19	590	22	0.01	<5	422	0.29	35	60	47
B291020		3.68	0.74	172	1	1.61	19	570	22	0.05	<5	447	0.29	34	20	34
B291021		4.04	0.69	154	3	1.53	18	550	22	0.04	<5	408	0.27	32	100	36
B291022		3.43	0.66	174	1	1.51	18	530	22	0.02	<5	404	0.26	32	40	42
B291023		3.76	0.78	236	1	1.74	21	600	22	0.01	<5	447	0.30	39	50	48
B291024		4.10	0.76	199	1	1.57	20	610	23	0.01	<5	450	0.30	37	50	46
B291025		3.78	0.72	199	1	1.60	20	580	22	0.01	<5	429	0.29	36	40	47
B291026		3.93	0.73	190	1	1.61	21	630	23	0.02	<5	442	0.31	37	20	43
B291027		3.86	0.50	194	1	1.39	17	570	23	0.01	<5	324	0.29	35	30	41
B291028		3.75	0.73	192	1	1.52	20	580	20	0.01	<5	407	0.29	36	30	57
B291029																
B291030		2.12	0.56	356	8	0.12	440	320	141	0.02	12	49	0.21	86	30	577
B291031		3.98	0.57	138	1	1.45	16	600	22	0.01	6	337	0.28	35	30	36
B291032		4.37	0.50	129	1	1.23	15	490	24	0.03	<5	320	0.21	25	20	23
B291033		3.96	0.77	227	1	1.57	20	600	24	0.01	<5	424	0.30	36	40	38
B291034		3.70	0.84	217	1	1.74	20	630	24	0.01	<5	467	0.32	39	20	40
B291035		3.54	0.83	231	2	1.70	21	650	22	0.02	<5	482	0.33	41	20	40
B291036		0.03	11.75	156	<1	0.01	2	500	3	0.02	<5	108	<0.01	2	<10	7
B291037		4.12	0.76	203	1	1.57	20	570	23	0.02	<5	394	0.28	35	20	36
B291038		3.41	0.86	274	1	1.41	19	600	22	0.01	9	393	0.30	36	20	41
B291039		3.42	0.76	263	1	1.49	18	580	26	0.01	8	402	0.30	36	20	74
B291040		3.63	0.76	289	<1	1.69	21	620	30	0.01	6	470	0.31	37	20	71

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291041		0.42	0.895	2.7	7.68	1090	990	3.1	54	1.56	0.5	8	27	130	2.03	0.04
B291042		0.34	0.222	1.2	7.13	1390	860	3.0	13	1.17	<0.5	6	50	96	2.07	0.03
B291043		2.86	0.027	<0.5	7.76	309	1740	3.1	2	2.52	<0.5	9	30	22	2.56	0.01
B291044		3.74	0.353	<0.5	7.82	382	1630	3.1	7	2.19	<0.5	7	41	37	2.43	0.01
B291045		3.88	0.170	<0.5	7.86	1210	1650	3.2	29	2.02	<0.5	9	32	56	2.49	<0.01
B291046		4.14	0.142	<0.5	7.37	891	1560	3.0	17	2.17	<0.5	8	42	46	2.25	<0.01
B291047		4.08	0.191	<0.5	8.06	2300	1650	3.2	16	2.11	<0.5	9	30	81	2.46	0.01
B291048		4.10	0.106	<0.5	6.30	354	1260	2.4	4	1.73	<0.5	6	32	25	1.89	<0.01
B291049		0.04	0.094													
B291050		0.10	0.090	<0.5	7.22	113	590	2.8	<2	0.48	<0.5	58	1170	394	8.09	0.03
B291051		2.38	0.103	<0.5	7.67	419	1550	3.3	5	1.95	<0.5	8	29	36	2.30	0.01
B291052		2.08	0.058	<0.5	8.48	284	1680	3.4	2	2.04	<0.5	9	41	51	2.48	<0.01
B291053		4.60	0.043	<0.5	7.83	250	1600	3.3	4	2.11	<0.5	7	27	27	2.37	<0.01
B291054		4.06	5.58	<0.5	7.79	367	1660	2.9	559	2.02	<0.5	9	40	42	2.43	<0.01
B291055		3.42	0.279	<0.5	7.26	255	1580	3.2	3	1.95	<0.5	7	28	37	2.29	<0.01
B291056		1.44	<0.005	<0.5	0.12	<5	10	<0.5	<2	17.70	<0.5	1	4	2	0.11	<0.01
B291057		2.98	0.222	<0.5	8.39	427	1630	3.3	<2	2.19	<0.5	8	26	22	2.35	<0.01
B291058		5.40	0.025	<0.5	7.98	142	1410	2.9	<2	1.89	<0.5	6	38	30	2.02	<0.01
B291059		2.38	0.114	<0.5	7.66	237	1660	3.0	2	2.21	<0.5	8	27	21	2.31	0.01
B291060		0.60	1.805	<0.5	7.35	237	1510	2.8	42	2.10	<0.5	13	42	114	2.48	<0.01
B291061		2.74	0.196	<0.5	7.70	202	1590	3.0	10	2.06	<0.5	8	28	40	2.31	<0.01
B291062		1.88	0.189	<0.5	8.25	267	1640	3.3	11	2.15	<0.5	10	43	46	2.46	<0.01
B291063		1.46	0.698	<0.5	7.63	227	1690	3.2	2	2.05	<0.5	9	30	46	2.45	<0.01
B291064		3.28	0.089	<0.5	7.11	138	1360	2.9	<2	1.63	<0.5	6	35	26	1.93	<0.01
B291065		1.18	0.016	<0.5	7.18	130	1250	3.1	<2	1.68	<0.5	6	24	13	1.90	<0.01
B291066		2.62	0.148	<0.5	8.05	437	1590	3.5	8	2.06	<0.5	9	42	32	2.35	0.01
B291067		2.30	0.049	<0.5	7.73	663	1570	3.2	<2	2.12	<0.5	9	31	25	2.28	<0.01
B291068		2.70	0.077	0.6	7.66	519	1560	3.3	3	1.76	<0.5	7	39	197	2.13	<0.01
B291069		0.04	0.071													
B291070		0.12	0.809	2.6	7.70	13	430	0.7	<2	1.68	<0.5	21	101	2010	4.69	<0.01
B291071		2.22	0.533	<0.5	7.63	563	1480	3.4	17	1.95	<0.5	9	25	50	2.25	<0.01
B291072		1.90	0.235	<0.5	7.47	549	1460	2.9	23	1.48	<0.5	9	40	54	1.97	<0.01
B291073		1.20	0.233	0.6	7.49	304	1470	3.3	8	1.70	<0.5	9	26	152	2.22	<0.01
B291074		2.96	0.104	<0.5	7.42	281	1610	3.2	11	1.90	<0.5	10	42	40	2.25	<0.01
B291075		1.24	0.126	<0.5	7.40	416	1350	2.8	13	1.63	<0.5	10	24	36	2.03	<0.01
B291076		1.68	<0.005	<0.5	0.15	7	20	<0.5	<2	18.15	<0.5	1	4	2	0.12	<0.01
B291077		4.14	0.154	<0.5	7.61	167	1510	3.4	2	1.95	<0.5	7	29	25	2.21	<0.01
B291078		3.74	0.356	<0.5	6.99	129	1380	3.0	9	1.95	<0.5	6	35	22	2.01	0.01
B291079		2.44	9.99	<0.5	7.44	156	1640	3.0	434	2.20	<0.5	8	29	27	2.32	<0.01
B291080		2.12	0.692	<0.5	7.50	227	1660	3.0	13	2.06	<0.5	8	41	36	2.35	<0.01

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291041		3.84	0.50	373	2	0.22	16	630	170	0.07	76	120	0.30	39	30	120
B291042		3.57	0.48	276	2	0.18	11	560	105	0.09	57	123	0.27	37	30	106
B291043		3.49	0.83	350	<1	1.75	22	660	34	0.01	6	496	0.35	41	10	89
B291044		3.89	0.77	289	2	1.68	20	620	32	0.03	6	456	0.31	36	30	76
B291045		3.82	0.80	258	<1	1.68	21	630	30	0.07	<5	466	0.31	39	50	59
B291046		3.78	0.78	238	2	1.66	21	590	27	0.05	<5	460	0.30	37	80	59
B291047		4.32	0.82	238	2	1.60	20	650	33	0.09	<5	476	0.33	40	40	60
B291048		2.81	0.64	201	1	1.36	16	520	20	0.02	<5	378	0.25	30	20	53
B291049																
B291050		2.11	0.57	388	8	0.12	481	330	153	0.02	8	52	0.24	90	30	628
B291051		3.64	0.78	274	1	1.61	21	640	25	0.02	<5	457	0.31	38	20	75
B291052		3.97	0.79	283	<1	1.66	20	660	32	0.02	5	462	0.30	37	20	75
B291053		3.49	0.78	314	<1	1.60	22	640	30	0.01	<5	452	0.30	37	10	83
B291054		3.58	0.80	266	1	1.62	20	680	36	0.02	5	472	0.30	39	10	64
B291055		3.64	0.77	296	<1	1.57	21	630	29	0.01	<5	434	0.30	38	10	85
B291056		0.03	10.85	153	<1	0.01	4	460	<2	0.01	<5	108	<0.01	2	<10	7
B291057		3.93	0.79	279	<1	1.60	24	680	29	0.01	11	438	0.30	38	30	63
B291058		4.22	0.65	242	1	1.72	19	620	35	0.02	<5	454	0.26	32	10	62
B291059		3.49	0.75	296	<1	1.70	20	640	30	0.02	<5	501	0.31	38	10	74
B291060		3.32	0.72	253	2	1.52	20	610	22	0.43	<5	471	0.29	35	10	56
B291061		3.68	0.69	279	<1	1.62	21	620	32	0.13	<5	463	0.28	36	20	75
B291062		3.92	0.72	287	1	1.70	20	640	35	0.20	6	474	0.29	36	40	76
B291063		3.68	0.75	269	<1	1.68	23	640	24	0.04	<5	498	0.32	40	40	62
B291064		3.68	0.60	229	<1	1.50	18	520	31	0.03	<5	400	0.25	30	20	58
B291065		3.43	0.59	271	<1	1.58	17	490	34	0.01	<5	380	0.24	30	10	64
B291066		3.72	0.71	288	<1	1.72	20	620	36	0.03	<5	478	0.30	37	10	70
B291067		3.64	0.71	312	<1	1.74	21	630	38	0.03	<5	467	0.31	38	10	85
B291068		3.62	0.72	235	2	1.68	65	610	29	0.02	<5	484	0.29	36	700	195
B291069																
B291070		1.66	1.24	419	2	3.00	49	620	23	0.56	<5	207	0.29	89	<10	213
B291071		3.86	0.70	276	1	1.63	20	580	32	0.05	<5	437	0.29	36	20	77
B291072		4.00	0.62	194	1	1.48	16	560	26	0.03	<5	411	0.25	32	30	57
B291073		3.89	0.64	266	<1	1.58	44	560	39	0.01	<5	393	0.26	32	370	165
B291074		3.60	0.72	247	1	1.62	20	650	24	0.02	<5	466	0.31	38	20	62
B291075		3.84	0.63	219	3	1.49	19	560	27	0.10	<5	408	0.25	31	80	50
B291076		0.03	11.05	157	<1	0.01	2	480	2	0.01	<5	116	0.01	1	<10	8
B291077		3.64	0.71	280	5	1.70	18	590	31	0.06	<5	454	0.29	36	90	65
B291078		3.53	0.63	287	3	1.62	16	540	33	0.02	<5	412	0.26	32	10	63
B291079		3.61	0.73	303	3	1.59	22	610	30	0.07	5	474	0.30	38	40	63
B291080		3.87	0.77	278	1	1.66	18	650	28	0.12	5	483	0.30	38	40	59

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B291081		0.82	0.682	<0.5	7.82	222	1550	3.0	13	1.88	<0.5	13	25	75	2.34	0.01
B291082		0.88	0.443	<0.5	7.40	112	1530	2.8	4	1.89	<0.5	8	40	57	2.27	0.01
B291083		2.54	0.601	<0.5	7.47	293	1490	3.0	23	1.81	<0.5	10	26	45	2.41	0.01
B291084		0.98	2.53	66.2	4.98	>10000	110	2.2	202	0.59	9.3	51	35	6420	12.80	0.20
B291085		5.38	0.348	0.5	7.32	859	1580	3.0	12	2.03	0.8	13	29	89	3.04	0.02
B291086		5.78	0.757	0.7	7.20	657	1580	3.0	14	2.04	<0.5	10	39	47	2.37	0.01
B291087		4.96	0.230	<0.5	7.74	255	1680	3.0	11	2.15	<0.5	9	30	30	2.51	0.01
B291088		4.92	0.135	<0.5	7.05	188	1600	3.1	7	2.18	<0.5	10	40	33	2.40	0.01
B291089		0.04	0.187													
B291090		0.12	0.090	<0.5	7.54	112	610	2.9	<2	0.54	<0.5	62	1235	418	9.05	0.03
B291091		1.48	0.468	<0.5	7.14	78	1340	3.0	37	1.84	<0.5	8	24	21	2.08	0.01
B291092		2.82	0.837	1.3	7.07	1510	1380	2.6	22	1.58	1.0	19	38	81	2.71	0.02
B291093		1.56	0.180	<0.5	6.78	228	1540	2.6	7	1.68	<0.5	8	25	45	2.20	0.01
B291094		3.66	0.190	<0.5	6.76	304	1400	2.6	5	2.14	<0.5	10	34	35	2.23	0.01
B291095		3.14	0.242	0.6	6.87	101	1480	2.5	19	2.09	<0.5	8	23	67	2.34	0.02
B291096		1.48	0.065	<0.5	0.12	<5	20	<0.5	<2	19.15	<0.5	1	2	2	0.12	<0.01
B291097		0.80	9.53	0.9	6.39	174	1100	2.5	223	2.29	5.8	27	18	68	2.76	<0.01
B291098		0.96	0.657	0.5	7.33	493	950	5.0	29	1.77	20.0	35	28	542	3.14	0.03
B291099		2.86	0.261	1.6	7.89	986	770	3.7	8	0.69	4.2	13	22	228	3.69	0.05
B291100		3.16	0.412	1.8	7.19	1330	590	2.9	5	1.73	6.2	17	39	60	4.05	0.13
B291101		1.54	0.240	1.7	7.18	565	610	2.7	6	1.83	4.1	3	16	56	2.70	0.13
B291102		1.32	0.125	1.5	7.48	641	610	2.9	8	2.05	4.3	3	33	62	2.79	0.11
B291103		2.32	0.073	0.7	7.55	766	390	2.7	3	1.18	3.6	5	21	42	2.21	0.08
B291104		2.40	0.105	0.8	6.82	456	800	3.0	5	2.02	1.4	7	38	75	2.41	0.03
B291105		3.48	0.162	<0.5	6.91	126	1370	2.5	8	2.31	<0.5	9	22	96	2.23	0.01
B291106		4.76	0.197	<0.5	6.98	136	1400	2.8	12	2.45	<0.5	9	37	64	2.45	0.01
B291107		1.98	4.00	<0.5	6.96	790	1300	2.7	22	2.81	<0.5	17	24	86	2.59	0.01
B291108		3.34	0.064	<0.5	7.26	130	1670	3.1	3	2.05	<0.5	9	35	32	2.32	0.01
B291109		0.04	0.068													
B291110		0.10	3.18	<0.5	7.42	6	2150	3.7	<2	4.84	<0.5	26	144	106	5.39	0.02
B291111		2.68	0.470	0.8	6.21	234	320	2.8	16	2.44	1.9	9	16	51	2.20	0.08
B291112		3.32	0.767	1.4	6.32	240	540	2.6	43	2.21	<0.5	7	39	58	2.13	0.02
B291113		6.32	0.831	<0.5	7.46	230	1480	2.9	48	2.02	<0.5	12	26	53	2.35	0.01

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05042605

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291081		3.81	0.69	257	2	1.53	21	600	29	0.25	<5	437	0.27	34	20	57
B291082		3.63	0.69	252	2	1.54	19	610	26	0.22	6	442	0.27	35	40	56
B291083		3.50	0.69	351	1	1.36	21	670	28	0.08	27	402	0.30	38	10	202
B291084		2.18	0.28	231	14	0.07	16	460	2060	6.79	3930	428	0.10	20	30	584
B291085		3.59	0.53	409	2	1.31	22	660	55	0.12	47	347	0.31	40	20	277
B291086		3.77	0.64	297	2	1.50	19	610	42	0.12	21	401	0.29	36	50	114
B291087		3.69	0.77	296	1	1.65	20	670	32	0.07	11	466	0.32	39	20	126
B291088		3.83	0.70	286	8	1.73	20	640	29	0.09	5	464	0.30	37	50	92
B291089																
B291090		2.36	0.62	407	9	0.13	497	380	160	0.02	14	54	0.25	97	40	648
B291091		3.48	0.62	274	<1	1.68	18	550	42	0.05	7	409	0.27	33	20	77
B291092		3.88	0.44	338	6	0.83	20	610	124	0.30	66	229	0.26	34	60	171
B291093		3.51	0.59	248	4	1.36	20	590	23	0.06	10	382	0.28	35	110	73
B291094		3.65	0.56	386	3	1.31	20	570	44	0.04	21	357	0.28	35	40	175
B291095		3.56	0.53	406	3	1.38	17	590	55	0.06	37	359	0.27	34	40	185
B291096		0.04	11.35	152	<1	0.01	2	480	3	<0.01	<5	104	0.01	2	<10	8
B291097		3.28	0.41	2380	2	1.12	33	490	83	0.06	55	289	0.24	30	40	1440
B291098		3.17	0.42	4740	2	0.64	39	590	144	1.01	90	208	0.30	39	30	3580
B291099		3.43	0.41	826	3	0.18	23	690	291	0.61	189	194	0.23	35	40	857
B291100		3.21	0.61	2300	5	0.02	14	550	924	1.27	432	74	0.22	32	50	1110
B291101		3.25	0.63	1730	9	0.02	6	570	423	0.45	224	74	0.22	30	120	344
B291102		3.35	0.68	1935	8	0.02	7	590	419	0.34	244	81	0.25	35	70	396
B291103		3.16	0.47	861	3	0.03	12	570	189	0.18	140	59	0.24	31	40	366
B291104		3.71	0.59	566	2	0.28	17	540	64	0.27	57	184	0.24	31	100	246
B291105		4.38	0.56	236	<1	1.28	16	580	24	0.34	11	388	0.26	32	90	35
B291106		3.77	0.73	272	<1	1.47	17	610	28	0.29	20	415	0.28	36	40	45
B291107		3.86	0.71	294	1	1.40	20	590	23	0.40	20	446	0.27	34	30	43
B291108		3.88	0.66	282	1	1.41	21	590	29	0.12	18	404	0.29	35	50	61
B291109																
B291110		3.71	3.07	1110	13	2.57	67	2430	30	0.33	<5	1780	0.39	181	10	104
B291111		2.55	0.57	411	2	0.06	16	490	142	0.44	38	168	0.21	26	80	261
B291112		2.87	0.69	318	2	0.69	15	530	71	0.27	40	253	0.24	31	210	150
B291113		3.89	0.67	240	2	1.39	20	600	45	0.25	15	399	0.28	35	40	47

Comments: Check assays for sample B291074 report 0.152ppm gold and 0.189ppm gold.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da / -JUN-2005
Account: STRGOL

CERTIFICATE VA05045435

Project: Dublin Gulch-1735

P.O. No.:

This report is for 185 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 9-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291114		6.36	0.035			<0.5	6.64	416	1590	2.8	2	2.46	<0.5	8	79	36
B291115		6.28	0.131			<0.5	6.70	1930	1170	2.5	7	2.44	<0.5	9	92	73
B291116		1.70	<0.005			<0.5	0.13	5	20	<0.5	<2	18.55	<0.5	<1	7	2
B291117		5.82	0.022			<0.5	7.15	222	1390	3.0	2	2.45	<0.5	7	92	28
B291118		6.06	0.036			<0.5	7.35	351	1560	3.1	2	2.46	<0.5	8	78	48
B291119		5.64	0.159			<0.5	7.17	247	1610	2.9	7	2.24	<0.5	10	94	47
B291120		2.56	0.035			<0.5	7.51	68	1570	3.1	<2	2.52	<0.5	8	79	27
B291121		2.06	0.466			<0.5	7.67	285	1670	1.9	24	2.47	<0.5	16	79	166
B291122		1.70	0.477			<0.5	7.17	161	1660	1.7	25	2.48	<0.5	11	77	188
B291123		3.02	0.313			<0.5	7.82	420	1760	2.1	15	2.44	<0.5	13	88	138
B291124		6.24	0.090			<0.5	7.60	322	1570	2.9	3	2.46	<0.5	9	97	36
B291125		2.88	0.470			2.5	7.16	252	580	2.7	18	2.93	3.5	11	101	37
B291126		3.56	0.041			<0.5	7.49	369	1160	2.9	<2	2.79	<0.5	7	90	27
B291127		3.82	0.192			<0.5	7.51	198	1720	3.0	15	2.39	<0.5	9	99	63
B291128		3.14	0.237			<0.5	7.03	332	1580	3.1	7	2.48	<0.5	9	94	53
B291129		0.04	0.294													
B291130		0.10	0.479			2.6	9.13	6	1100	1.2	<2	1.50	<0.5	8	9	7460
B291131		4.12	0.256			4.0	7.03	2720	800	2.7	8	2.65	3.0	13	116	121
B291132		2.28	0.037			<0.5	7.55	445	1700	3.0	<2	2.86	<0.5	11	115	27
B291133		2.66	0.082			<0.5	7.55	819	1520	3.0	3	2.24	<0.5	8	107	41
B291134		1.68	0.062			<0.5	7.70	200	1740	3.3	<2	2.34	<0.5	9	96	41
B291135		0.98	0.125			<0.5	7.58	347	1630	2.8	2	2.26	<0.5	18	112	63
B291136		1.52	<0.005			<0.5	0.12	<5	20	<0.5	<2	19.70	<0.5	<1	4	1
B291137		5.88	0.926			<0.5	7.30	107	1560	2.9	8	2.45	<0.5	9	119	41
B291138		4.30	0.716			0.8	7.31	217	1130	2.9	28	2.14	<0.5	11	99	50
B291139		5.22	0.413			<0.5	7.60	95	1650	2.9	3	2.32	<0.5	8	111	36
B291140		5.84	0.972			1.2	7.68	166	1610	3.1	17	2.45	<0.5	7	91	24
B291141		2.02	0.049			<0.5	7.73	378	1390	3.4	<2	2.16	<0.5	8	120	21
B291142		1.72	0.062			<0.5	6.79	742	1240	3.4	<2	2.01	<0.5	7	99	24
B291143		6.04	0.165			0.8	6.75	220	1140	2.9	6	1.82	1.9	7	116	42
B291144		4.98	0.492			0.7	7.53	265	1320	2.9	14	2.49	<0.5	9	94	41
B291145		3.74	1.195			0.7	6.98	335	1170	2.7	14	2.66	<0.5	9	106	41
B291146		5.20	3.28			<0.5	7.52	444	1620	2.8	20	2.34	<0.5	14	100	77
B291147		4.24	0.478			<0.5	7.63	156	1590	3.0	14	2.41	<0.5	11	117	46
B291148		3.96	0.628			1.1	7.29	568	1570	2.9	52	2.13	<0.5	7	96	33
B291149		0.04	0.621													
B291150		0.10	0.475			2.6	9.21	<5	1110	1.2	<2	1.52	<0.5	8	9	7530
B291151		3.54	0.425			0.8	6.80	1050	940	2.5	7	2.43	0.5	11	128	73
B291152		1.94	0.288			<0.5	7.43	241	1630	3.1	3	2.33	<0.5	13	108	37
B291153		3.04	0.655			0.5	6.52	401	1110	2.9	47	2.50	<0.5	8	117	57

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291114		2.24	0.01	3.81	0.72	247	8	1.42	19	590	21	0.15	9	416	0.29	36
B291115		2.30	0.01	3.39	0.64	265	35	1.24	21	520	23	0.40	9	373	0.27	32
B291116		0.12	<0.01	0.04	11.30	165	<1	0.02	3	460	<2	0.02	<5	108	<0.01	3
B291117		2.15	<0.01	3.63	0.73	278	1	1.61	20	580	23	0.14	5	446	0.29	35
B291118		2.24	<0.01	3.90	0.77	256	3	1.57	21	610	18	0.22	8	469	0.31	37
B291119		2.40	0.01	3.68	0.86	275	1	1.51	20	620	25	0.17	10	437	0.31	37
B291120		2.38	<0.01	3.63	0.78	301	1	1.64	21	620	25	0.16	6	471	0.31	37
B291121		2.51	<0.01	7.09	0.64	192	2	0.86	14	630	16	0.78	5	442	0.24	33
B291122		2.25	<0.01	6.85	0.51	191	6	0.84	14	610	16	0.74	<5	432	0.24	30
B291123		2.33	<0.01	6.33	0.66	227	2	1.19	17	670	28	0.42	8	467	0.32	36
B291124		2.38	0.01	3.81	0.76	282	1	1.56	20	630	28	0.17	7	429	0.31	37
B291125		2.26	0.09	3.21	0.81	714	1	0.57	22	560	373	0.16	23	298	0.27	34
B291126		2.35	0.01	3.57	0.64	386	1	1.50	18	600	21	0.12	10	396	0.30	37
B291127		2.30	0.01	4.34	0.73	257	1	1.52	21	620	20	0.27	10	481	0.31	38
B291128		2.36	<0.01	3.87	0.77	266	10	1.66	22	630	23	0.26	6	508	0.31	38
B291129																
B291130		3.30	0.03	3.77	1.23	497	2	3.42	11	1940	8	0.24	<5	690	0.35	179
B291131		3.04	0.08	3.33	0.89	1140	3	0.32	21	530	748	1.30	333	288	0.25	32
B291132		2.68	0.01	3.71	0.88	429	1	1.64	25	650	28	0.12	19	518	0.33	47
B291133		2.33	0.01	4.02	0.72	375	4	1.13	20	620	26	0.21	12	386	0.30	36
B291134		2.48	0.01	3.81	0.81	280	2	1.67	21	640	24	0.17	9	491	0.32	39
B291135		2.47	0.01	4.55	0.73	267	10	1.23	24	620	23	0.44	11	421	0.29	34
B291136		0.10	<0.01	0.03	11.95	176	<1	0.01	3	520	<2	0.01	<5	110	<0.01	3
B291137		2.40	0.01	3.84	0.84	288	1	1.49	22	610	22	0.17	9	452	0.30	38
B291138		2.16	0.01	4.13	0.66	459	2	0.88	19	540	66	0.32	23	298	0.26	33
B291139		2.45	0.01	4.12	0.77	370	1	1.36	22	620	43	0.22	17	432	0.30	37
B291140		2.42	0.01	3.99	0.79	350	2	1.47	21	600	94	0.14	34	446	0.30	36
B291141		2.18	0.01	3.75	0.74	260	1	1.72	18	540	29	0.12	6	455	0.28	33
B291142		1.94	0.01	3.95	0.61	225	<1	1.65	16	480	27	0.14	<5	421	0.25	29
B291143		1.92	0.04	3.77	0.60	359	1	0.89	15	410	120	0.28	21	271	0.21	25
B291144		2.38	0.01	3.91	0.78	390	1	1.05	21	650	50	0.31	25	367	0.31	39
B291145		2.42	0.02	3.55	0.79	459	8	0.97	21	610	86	0.29	35	344	0.29	37
B291146		2.93	0.01	3.88	0.90	314	1	1.22	25	640	33	0.46	25	402	0.30	41
B291147		2.55	0.01	4.02	0.85	288	2	1.53	23	630	21	0.24	7	477	0.30	37
B291148		2.37	0.02	3.84	0.71	279	1	1.43	21	600	110	0.25	51	406	0.29	36
B291149																
B291150		3.33	0.03	3.81	1.24	499	2	3.44	11	1940	10	0.24	<5	699	0.35	178
B291151		2.52	0.02	3.42	0.96	367	4	0.93	19	560	48	0.54	17	303	0.25	32
B291152		2.47	<0.01	3.82	0.79	265	1	1.68	20	640	25	0.20	5	499	0.31	39
B291153		2.39	0.02	3.48	0.76	399	2	1.25	19	570	86	0.26	28	357	0.28	35

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	ME-ICP61
	Analyte	W	Zn
	Units	ppm	ppm
	LOR	10	2
B291114		30	47
B291115		100	57
B291116		<10	7
B291117		20	54
B291118		50	46
B291119		20	72
B291120		10	59
B291121		90	18
B291122		150	17
B291123		70	42
B291124		20	54
B291125		30	692
B291126		30	56
B291127		20	46
B291128		120	48
B291129			
B291130		<10	58
B291131		30	566
B291132		20	83
B291133		20	62
B291134		10	48
B291135		80	56
B291136		<10	7
B291137		30	45
B291138		40	92
B291139		20	109
B291140		20	112
B291141		10	51
B291142		10	43
B291143		20	362
B291144		20	107
B291145		80	99
B291146		50	71
B291147		100	52
B291148		50	83
B291149			
B291150		<10	57
B291151		40	126
B291152		30	55
B291153		40	142

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291154		5.62	1.525			0.6	7.54	383	1550	3.0	80	2.07	<0.5	9	108	37
B291155		6.38	0.359			<0.5	7.20	111	790	1.5	13	0.89	<0.5	3	100	26
B291156		1.90	<0.005			<0.5	0.16	<5	20	<0.5	<2	19.40	<0.5	1	7	2
B291157		5.72	0.860			<0.5	7.14	162	850	2.0	12	1.16	<0.5	5	90	23
B291158		2.22	0.174			<0.5	6.85	423	760	1.4	5	0.87	<0.5	7	73	5
B291159		3.70	0.141			<0.5	7.30	261	1530	2.9	<2	2.34	<0.5	8	105	35
B291160		2.66	0.206			<0.5	7.47	493	1590	2.6	11	2.29	<0.5	10	110	32
B291161		1.62	0.211			<0.5	6.70	114	1010	1.0	5	0.84	<0.5	1	88	13
B291162		1.64	0.145			<0.5	6.91	173	1100	1.0	3	0.90	<0.5	2	82	20
B291163		1.36	>10.0			0.8	0.95	1500	60	0.5	464	0.67	<0.5	44	219	253
B291164		3.78	0.884			<0.5	7.42	103	1370	2.6	8	1.45	<0.5	9	108	69
B291165		2.00	0.194			<0.5	7.05	37	1480	1.0	9	0.63	<0.5	2	80	19
B291166		1.02	1.490			4.9	6.54	836	290	2.6	16	2.63	7.6	8	67	174
B291167		3.46	1.240			1.3	7.42	119	910	2.5	14	2.20	2.4	6	110	36
B291168		2.82	0.261			0.6	7.73	89	1200	3.0	13	2.37	<0.5	7	95	37
B291169		0.04	0.265													
B291170		0.10	0.462			2.7	9.72	10	1180	1.3	<2	1.63	<0.5	9	10	7800
B291171		1.34	0.212			<0.5	7.75	143	1580	3.1	3	1.76	<0.5	8	123	55
B291172		2.52	0.091			<0.5	7.98	84	1260	3.0	<2	1.92	<0.5	10	117	35
B291173		3.98	0.096			<0.5	7.89	788	1760	3.2	3	2.35	<0.5	9	102	20
B291174		4.70	1.550			<0.5	7.96	548	1740	2.9	35	2.58	<0.5	10	106	32
B291175		1.98	5.13			<0.5	7.14	275	1600	2.8	38	1.95	<0.5	9	95	35
B291176		1.96	0.005			<0.5	0.20	<5	30	<0.5	<2	20.7	<0.5	<1	10	2
B291177		4.18	0.404			<0.5	7.34	140	1650	3.0	10	2.14	<0.5	9	84	27
B291178		5.80	1.840			<0.5	7.10	283	1420	2.9	46	2.45	<0.5	10	74	40
B291179		5.42	2.85			2.0	7.78	1070	1740	2.8	138	2.15	<0.5	21	93	92
B291180		6.32	0.304			<0.5	7.29	249	1680	3.1	10	2.39	<0.5	10	66	34
B291181		2.24	0.865			1.1	7.99	335	1040	2.9	16	2.55	<0.5	11	114	42
B291182		1.46	1.545			<0.5	7.55	123	1210	3.1	19	2.64	<0.5	9	93	37
B291183		2.74	0.622			2.5	6.84	1255	440	2.3	11	0.84	6.8	5	124	40
B291184		6.22	0.264			2.8	8.13	343	720	3.0	6	1.88	2.6	6	81	52
B291185		0.68	8.12			10.5	2.29	>10000	130	0.9	48	0.48	11.1	54	134	31
B291186		5.46	0.724			1.8	7.02	166	430	2.0	4	1.18	7.1	2	75	15
B291187		3.24	0.236			0.5	6.42	95	800	1.5	4	0.97	<0.5	2	110	13
B291188		3.94	0.463			0.6	7.12	726	1530	2.9	17	2.09	<0.5	7	80	37
B291189		0.04	0.311													
B291190		0.10	0.092			<0.5	6.86	98	570	2.6	<2	0.51	<0.5	55	1135	392
B291191		3.56	1.395			<0.5	7.11	286	1500	2.6	18	2.34	<0.5	8	112	51
B291192		6.30	1.175			<0.5	6.91	56	1340	2.9	26	1.67	<0.5	6	87	44
B291193		6.08	0.368			<0.5	7.16	65	1500	3.0	11	2.22	<0.5	8	110	35

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291154		2.38	0.02	4.01	0.70	265	2	1.54	20	610	64	0.22	20	452	0.30	37
B291155		0.79	0.01	6.47	0.23	70	3	1.16	9	460	37	0.14	<5	283	0.08	9
B291156		0.13	<0.01	0.05	11.90	177	<1	0.02	3	540	2	0.01	<5	116	0.01	3
B291157		1.04	0.01	5.58	0.35	96	1	1.28	10	500	28	0.13	<5	323	0.12	14
B291158		0.67	<0.01	6.58	0.23	71	1	1.05	6	520	31	0.06	<5	282	0.08	9
B291159		2.36	<0.01	3.93	0.74	254	2	1.64	20	630	23	0.19	<5	476	0.30	36
B291160		2.33	0.01	3.95	0.72	272	16	1.48	24	640	23	0.15	12	449	0.30	35
B291161		0.53	0.02	6.50	0.30	81	<1	0.94	5	420	33	0.06	<5	243	0.04	3
B291162		0.58	0.02	6.52	0.32	84	<1	0.93	4	430	33	0.07	6	245	0.04	4
B291163		1.61	<0.01	0.40	0.18	56	3	0.06	45	50	32	1.12	36	46	0.02	3
B291164		2.21	0.01	4.27	0.70	195	<1	1.31	20	650	18	0.25	16	324	0.29	35
B291165		0.46	0.02	6.70	0.24	111	<1	0.74	5	410	60	0.10	24	205	0.03	3
B291166		6.73	0.13	3.20	0.86	2190	1	0.04	16	440	7140	5.80	2630	142	0.15	20
B291167		2.02	0.05	3.45	0.74	766	6	0.66	22	580	108	0.21	57	244	0.26	34
B291168		2.53	0.03	3.96	0.84	538	2	0.65	20	630	84	0.25	40	309	0.30	37
B291169																
B291170		3.53	0.03	3.98	1.30	528	2	3.58	11	2040	14	0.25	6	733	0.37	190
B291171		2.87	0.02	3.94	0.78	347	1	1.01	22	650	88	0.34	33	374	0.32	40
B291172		2.49	0.01	4.07	0.75	493	<1	0.58	19	630	49	0.45	29	290	0.32	39
B291173		2.46	0.01	3.76	0.68	261	1	1.68	23	690	23	0.15	19	492	0.34	41
B291174		2.57	0.01	4.12	0.72	276	1	1.53	22	690	22	0.21	14	472	0.33	41
B291175		2.25	0.01	3.91	0.67	204	3	1.27	23	590	49	0.21	22	405	0.30	37
B291176		0.15	<0.01	0.06	12.30	181	<1	0.02	7	570	8	0.03	<5	120	0.01	4
B291177		2.39	0.01	3.79	0.72	249	3	1.56	21	620	21	0.15	13	466	0.31	38
B291178		2.27	0.01	3.66	0.81	279	4	1.23	19	590	21	0.24	15	392	0.28	35
B291179		2.79	0.03	4.46	0.71	248	9	1.28	23	640	227	0.62	103	423	0.30	37
B291180		2.48	0.01	3.84	0.79	282	1	1.73	24	630	28	0.21	10	493	0.32	39
B291181		2.42	0.01	3.78	0.77	633	11	0.67	23	640	79	0.39	47	295	0.28	36
B291182		2.45	0.01	3.99	0.73	428	2	0.95	22	650	38	0.29	26	380	0.33	40
B291183		3.83	0.15	3.12	0.41	434	2	0.03	9	440	466	3.30	173	48	0.07	8
B291184		2.27	0.05	3.72	0.72	866	1	0.16	19	640	131	0.76	71	136	0.29	37
B291185		26.3	0.02	1.11	0.19	260	2	0.01	23	180	6030	>10.0	2660	24	0.05	7
B291186		1.02	0.15	3.06	0.38	512	<1	0.02	3	440	319	0.21	92	73	0.03	4
B291187		0.52	0.01	5.18	0.17	139	2	0.49	4	460	112	0.07	14	158	0.03	3
B291188		2.31	<0.01	3.98	0.72	211	2	1.68	19	630	24	0.23	<5	506	0.29	34
B291189																
B291190		8.39	0.03	2.23	0.58	370	9	0.12	453	340	145	0.02	10	52	0.21	87
B291191		2.31	0.01	4.25	0.65	219	7	1.41	21	650	20	0.27	17	453	0.29	35
B291192		2.19	0.01	3.68	0.86	181	2	1.32	23	610	24	0.17	19	433	0.28	34
B291193		2.28	0.01	3.74	0.70	226	6	1.70	18	620	24	0.18	8	487	0.30	36

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291154		60	67
B291155		30	14
B291156		<10	9
B291157		20	18
B291158		30	13
B291159		50	52
B291160		20	52
B291161		<10	4
B291162		<10	5
B291163		20	8
B291164		30	38
B291165		<10	73
B291166		20	1370
B291167		30	442
B291168		30	105
B291169			
B291170		<10	68
B291171		40	124
B291172		30	76
B291173		30	58
B291174		40	46
B291175		40	60
B291176		<10	15
B291177		30	51
B291178		30	47
B291179		960	51
B291180		20	60
B291181		40	138
B291182		30	60
B291183		10	1230
B291184		30	497
B291185		10	1810
B291186		10	1240
B291187		10	59
B291188		30	44
B291189			
B291190		30	593
B291191		70	45
B291192		30	35
B291193		20	47

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291194		2.12	0.107			<0.5	7.01	82	1350	2.8	6	1.73	<0.5	7	84	35
B291195		1.72	2.32			<0.5	6.37	66	840	1.2	12	0.74	<0.5	1	99	17
B291196		1.92	<0.005			<0.5	0.11	<5	10	<0.5	<2	18.50	<0.5	<1	1	2
B291197		1.96	0.817			<0.5	6.91	61	1270	2.6	38	1.44	<0.5	5	23	40
B291198		6.20	0.741			<0.5	7.18	105	1380	2.4	13	1.34	<0.5	8	25	56
B291199		6.26	1.950	2.51		<0.5	7.42	334	1610	2.2	31	1.48	<0.5	16	30	98
B291200		6.60	0.554			<0.5	7.14	104	1390	2.9	5	1.96	<0.5	7	29	41
B291201		3.30	0.154			<0.5	7.10	56	980	2.0	9	1.52	<0.5	3	12	26
B291202		3.20	0.228			0.5	6.97	31	930	1.9	6	1.33	<0.5	5	15	28
B291203		6.26	1.065			1.0	6.82	403	930	2.1	17	1.87	3.3	3	15	50
B291204		4.60	0.348			1.4	7.13	438	460	2.1	22	0.90	2.2	5	18	30
B291205		1.00	0.487			4.3	6.05	5630	440	2.3	21	2.79	6.2	17	14	95
B291206		6.24	0.586			1.8	7.47	1590	740	2.8	11	2.50	1.8	8	23	55
B291207		5.04	2.43			1.7	7.06	196	1590	3.1	24	2.25	<0.5	8	27	64
B291208		5.98	1.000			0.7	7.15	31	1410	2.8	16	2.16	<0.5	5	26	47
B291209		0.04	0.917													
B291210		0.10	3.28			0.9	6.81	17	1980	3.1	<2	4.50	<0.5	24	130	99
B291211		6.08	0.846			<0.5	6.92	110	1430	2.8	8	2.15	<0.5	7	26	32
B291212		5.72	1.270			<0.5	7.21	177	1520	3.0	17	2.31	<0.5	9	30	64
B291213		6.10	0.707			<0.5	7.30	371	1450	3.3	7	2.39	<0.5	7	28	48
B291214		6.16	0.554			<0.5	7.19	72	1390	3.2	8	2.15	<0.5	7	99	55
B291215		5.72	0.110			<0.5	7.39	46	1450	3.2	5	2.23	<0.5	6	93	32
B291216		1.86	0.005			<0.5	0.11	<5	20	<0.5	<2	18.20	<0.5	<1	7	2
B291217		5.98	0.853			<0.5	7.31	94	1320	3.0	16	2.08	<0.5	8	109	60
B291218		5.64	0.201			<0.5	6.96	128	1290	3.4	4	2.14	<0.5	6	107	45
B291219		6.48	0.910			<0.5	7.20	75	1210	3.3	14	1.75	<0.5	6	105	37
B291220		5.48	0.711			<0.5	6.76	60	900	2.1	29	1.21	<0.5	5	122	37
B291221		1.44	0.781			<0.5	7.35	66	1310	3.0	12	2.15	<0.5	6	110	46
B291222		1.84	3.25			<0.5	6.67	79	1250	3.0	14	2.17	<0.5	8	117	54
B291223		2.38	1.625			<0.5	7.04	128	1220	2.9	34	2.98	<0.5	9	99	60
B291224		5.94	1.745			<0.5	7.38	80	1280	2.9	36	2.26	<0.5	9	117	46
B291225		6.16	1.030			<0.5	7.20	73	1320	2.9	8	2.46	<0.5	8	114	49
B291226		5.78	0.899			<0.5	6.38	146	1360	2.9	14	2.26	<0.5	8	111	51
B291227		6.44	3.64			<0.5	7.28	75	1390	2.5	26	2.10	<0.5	8	97	45
B291228		5.04	2.17			0.5	7.00	84	1370	2.7	57	2.17	<0.5	7	115	52
B291229		0.04	2.35													
B291230		0.10	0.459			2.5	8.47	<5	1030	1.2	<2	1.43	<0.5	6	12	7230
B291231		6.52	2.19			<0.5	7.11	211	1370	2.7	36	2.20	<0.5	6	108	46
B291232		2.44	0.543			<0.5	6.77	46	1330	2.7	9	2.10	<0.5	7	114	43
B291233		1.94	2.29			<0.5	6.77	45	1220	2.5	53	2.16	<0.5	5	104	38

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291194		1.95	0.01	4.14	0.64	171	2	1.51	19	600	22	0.21	<5	438	0.26	31
B291195		0.74	0.01	5.40	0.31	67	1	0.82	9	430	31	0.04	<5	273	0.07	8
B291196		0.10	<0.01	0.03	10.80	138	<1	0.01	5	460	5	0.01	<5	122	<0.01	2
B291197		1.78	0.01	4.63	0.57	165	2	1.36	17	480	26	0.18	<5	385	0.22	28
B291198		2.09	0.01	4.51	0.69	152	<1	1.35	19	570	23	0.23	12	418	0.25	31
B291199		2.56	0.01	4.44	0.71	151	2	1.16	18	610	24	0.59	7	407	0.26	38
B291200		2.37	0.01	3.82	0.86	215	1	1.47	21	610	28	0.18	14	493	0.29	34
B291201		1.13	0.01	5.39	0.57	172	1	1.20	10	510	80	0.18	22	291	0.12	13
B291202		1.00	0.01	5.41	0.48	144	1	1.29	9	530	57	0.16	13	290	0.12	14
B291203		1.64	0.08	4.03	0.56	342	3	0.51	12	490	147	0.40	67	214	0.15	19
B291204		1.14	0.06	3.17	0.39	313	1	0.04	9	490	244	0.36	81	65	0.08	10
B291205		4.35	0.17	2.70	0.81	1890	5	0.03	12	410	788	2.24	199	116	0.14	21
B291206		2.45	0.04	3.69	0.78	777	2	0.13	20	610	194	0.51	59	158	0.27	34
B291207		2.36	0.01	4.06	0.68	246	3	1.44	20	600	65	0.32	40	428	0.28	35
B291208		2.27	0.02	4.05	0.72	295	4	1.07	19	620	73	0.24	30	350	0.28	35
B291209																
B291210		4.85	<0.01	3.48	2.81	986	13	2.36	60	2260	24	0.29	<5	1690	0.36	155
B291211		2.30	<0.01	3.90	0.75	258	1	1.66	21	580	25	0.16	6	469	0.28	34
B291212		2.36	<0.01	4.12	0.80	183	2	1.68	20	660	16	0.31	<5	495	0.30	36
B291213		2.38	0.01	3.65	0.95	208	2	1.79	20	670	19	0.23	<5	577	0.30	37
B291214		2.36	0.01	3.89	0.84	193	4	1.71	18	640	21	0.25	<5	538	0.30	36
B291215		2.30	0.01	3.73	0.80	231	1	1.76	18	630	25	0.16	<5	511	0.30	36
B291216		0.10	<0.01	0.03	10.65	141	<1	0.02	6	530	3	<0.01	<5	110	<0.01	1
B291217		2.22	0.01	4.09	0.71	225	3	1.48	18	620	34	0.30	<5	423	0.27	32
B291218		2.07	<0.01	3.92	0.68	222	3	1.51	15	560	33	0.23	6	421	0.25	32
B291219		1.96	0.01	4.28	0.62	184	4	1.55	15	520	25	0.19	6	424	0.23	31
B291220		1.49	0.01	5.07	0.53	118	6	1.29	11	510	23	0.15	5	333	0.16	24
B291221		2.30	<0.01	4.53	0.88	223	1	1.55	15	530	30	0.22	<5	490	0.25	39
B291222		2.27	<0.01	4.37	0.83	225	4	1.61	17	570	21	0.24	5	502	0.25	39
B291223		2.34	<0.01	3.87	0.80	230	6	1.52	19	580	19	0.30	7	454	0.28	39
B291224		2.48	<0.01	3.95	0.95	258	4	1.69	19	550	25	0.22	<5	521	0.26	42
B291225		2.58	<0.01	4.03	1.00	275	1	1.67	17	610	21	0.25	<5	536	0.28	45
B291226		2.40	<0.01	3.63	0.84	223	7	1.68	19	590	20	0.24	<5	518	0.28	40
B291227		2.44	<0.01	3.50	0.86	202	1	1.63	15	610	20	0.25	<5	499	0.25	35
B291228		2.45	<0.01	4.04	0.81	243	4	1.49	18	600	58	0.27	12	455	0.26	39
B291229																
B291230		3.26	0.02	3.69	1.10	477	3	3.51	10	1940	10	0.23	<5	681	0.32	162
B291231		2.41	<0.01	3.89	0.87	240	3	1.58	17	580	26	0.21	5	478	0.27	40
B291232		2.32	<0.01	3.76	0.80	220	2	1.63	16	570	24	0.23	<5	475	0.27	37
B291233		2.26	<0.01	3.99	0.82	294	1	1.44	12	550	44	0.14	14	411	0.24	39

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	ME-ICP61
	Analyte	W	Zn
	Units	ppm	ppm
	LOR	10	2
B291194		20	34
B291195		<10	9
B291196		<10	11
B291197		20	42
B291198		30	30
B291199		40	39
B291200		30	48
B291201		20	60
B291202		20	56
B291203		80	582
B291204		20	393
B291205		30	1150
B291206		30	303
B291207		30	64
B291208		30	93
B291209			
B291210		<10	89
B291211		40	53
B291212		40	26
B291213		30	30
B291214		50	31
B291215		20	39
B291216		<10	7
B291217		20	43
B291218		10	38
B291219		30	35
B291220		10	15
B291221		290	31
B291222		110	31
B291223		20	25
B291224		10	36
B291225		40	37
B291226		30	33
B291227		30	22
B291228		70	36
B291229			
B291230		<10	48
B291231		20	33
B291232		10	41
B291233		20	31

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291234		1.88	0.814			1.3	6.97	167	780	2.7	10	2.37	3.2	6	123	51
B291235		4.18	2.34			3.4	6.90	118	710	2.4	41	2.91	1.1	6	106	47
B291236		1.48	<0.005			<0.5	0.13	<5	20	<0.5	<2	18.80	<0.5	<1	9	3
B291237		2.32	5.08			1.2	6.95	101	1070	2.9	68	2.71	1.9	8	92	49
B291238		3.72	0.553			0.8	7.39	81	1460	3.0	7	2.29	0.5	7	125	55
B291239		3.36	0.989			<0.5	7.12	82	1500	2.9	9	2.55	<0.5	7	37	47
B291240		3.28	0.429			1.3	7.44	215	700	2.8	9	2.30	0.5	11	31	55
B291241		0.98	0.136			0.7	7.28	27	1230	2.7	2	2.04	<0.5	7	29	55
B291242		0.96	0.103			0.5	7.48	33	1290	2.8	2	1.84	<0.5	7	29	42
B291243		1.38	3.43			<0.5	7.28	15	1400	2.9	31	2.41	<0.5	8	31	45
B291244		0.86	1.050			<0.5	7.55	1565	1680	2.5	16	1.88	<0.5	81	30	169
B291245		3.64	0.468			<0.5	6.98	75	1390	2.8	7	2.24	<0.5	8	29	34
B291246		4.00	0.191			<0.5	6.87	31	1360	2.8	3	2.49	<0.5	5	32	35
B291247		2.24	0.336			<0.5	7.46	62	1440	2.9	11	2.33	<0.5	7	34	44
B291248		4.20	0.424			0.6	7.05	39	1520	2.8	10	2.17	<0.5	7	29	41
B291249		0.04	0.882													
B291250		0.10	0.451			2.4	9.18	<5	1050	1.2	2	1.46	<0.5	7	12	6950
B291251		1.96	0.923			0.5	7.25	420	1560	2.1	31	2.13	<0.5	25	28	85
B291252		6.00	0.553			<0.5	6.86	35	1350	2.5	15	2.11	<0.5	5	31	48
B291253		2.98	1.210			0.5	6.57	109	1320	2.5	21	2.26	0.5	10	32	61
B291254		3.16	0.410			0.5	6.89	55	1180	2.5	5	2.91	0.9	7	34	47
B291255		1.16	0.333			<0.5	7.26	109	1510	2.6	4	2.09	0.5	12	34	45
B291256		2.08	<0.005			<0.5	0.12	<5	20	<0.5	<2	19.00	<0.5	<1	2	2
B291257		4.46	0.224			0.7	6.39	971	590	2.8	<2	2.96	1.4	9	31	36
B291258		3.96	0.274			<0.5	7.23	25	1540	3.0	4	2.07	<0.5	8	57	27
B291259		3.58	1.310			0.5	7.41	75	1470	2.7	37	2.08	<0.5	9	35	58
B291260		5.96	0.470			<0.5	7.36	44	1390	3.1	7	2.30	<0.5	6	55	24
B291261		2.66	0.254			<0.5	7.20	79	1440	3.0	6	2.27	<0.5	8	28	36
B291262		2.38	0.169			<0.5	7.32	73	1450	3.0	3	2.33	<0.5	8	54	32
B291263		4.94	0.314			<0.5	7.88	67	1530	3.2	7	2.26	<0.5	9	33	51
B291264		3.48	1.070			<0.5	7.93	35	1470	3.2	24	2.08	<0.5	7	89	34
B291265		3.12	0.309			<0.5	7.67	18	1400	3.1	7	2.27	<0.5	6	106	27
B291266		2.82	1.460			<0.5	7.81	22	1420	3.1	5	2.25	<0.5	5	98	34
B291267		4.78	2.69			<0.5	7.61	269	1360	3.2	24	2.05	<0.5	12	113	63
B291268		4.80	>10.0			<0.5	7.74	91	1400	3.2	241	2.09	<0.5	7	100	49
B291269		0.04	>10.0													
B291270		0.10	1.370			<0.5	6.74	1190	670	5.7	<2	0.01	<0.5	5	199	37
B291271		1.50	0.312			<0.5	7.58	130	920	3.0	3	1.89	0.5	7	115	27
B291272		0.64	3.39			9.2	5.85	764	450	2.4	57	4.75	1.2	5	81	25
B291273		1.76	0.059			1.0	7.31	115	720	2.9	<2	1.52	<0.5	7	130	21

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291234		2.05	0.04	3.77	0.95	843	2	0.43	11	520	86	0.46	35	235	0.21	33
B291235		2.11	0.02	3.00	0.84	845	2	0.63	17	580	99	0.52	44	282	0.25	36
B291236		0.11	<0.01	0.04	10.75	145	<1	0.01	7	510	7	0.01	<5	112	0.01	2
B291237		1.92	0.02	3.29	0.63	548	3	0.69	17	560	157	0.33	22	279	0.27	38
B291238		2.51	0.01	3.54	0.83	390	2	1.52	19	640	53	0.24	19	431	0.29	40
B291239		2.47	<0.01	3.65	0.87	362	1	1.55	14	590	21	0.17	15	458	0.27	37
B291240		2.35	0.01	3.52	0.86	546	1	0.28	17	630	43	0.92	24	260	0.28	39
B291241		2.41	0.01	3.61	0.77	463	1	0.80	18	620	125	0.44	28	300	0.28	38
B291242		2.29	0.01	3.56	0.75	395	2	0.86	19	640	72	0.35	30	314	0.28	38
B291243		2.55	<0.01	3.94	0.77	255	1	1.60	16	600	20	0.33	5	505	0.28	39
B291244		3.61	<0.01	4.70	0.82	215	6	1.40	29	650	25	1.17	<5	436	0.27	41
B291245		2.40	<0.01	3.50	0.85	247	2	1.66	17	590	19	0.18	7	479	0.28	37
B291246		2.28	<0.01	3.65	0.85	251	1	1.65	18	580	22	0.15	<5	519	0.27	40
B291247		2.67	<0.01	3.70	0.99	304	2	1.75	15	630	28	0.20	<5	534	0.29	43
B291248		2.48	<0.01	3.72	0.87	256	3	1.69	17	630	24	0.18	8	494	0.29	37
B291249																
B291250		3.24	0.02	3.62	1.15	462	2	3.31	8	1890	9	0.23	<5	688	0.32	158
B291251		2.09	<0.01	4.99	0.71	238	19	0.99	19	580	23	0.34	13	397	0.25	32
B291252		2.31	0.01	3.88	0.77	289	<1	1.28	14	510	39	0.20	10	411	0.24	37
B291253		2.65	<0.01	3.72	0.86	361	30	1.10	13	620	58	0.32	12	375	0.27	40
B291254		2.69	0.01	3.78	0.88	496	2	0.93	14	620	58	0.30	9	364	0.28	44
B291255		2.72	<0.01	4.04	0.97	371	1	1.24	12	580	31	0.20	15	454	0.27	42
B291256		0.11	<0.01	0.04	10.90	144	<1	0.01	4	570	3	<0.01	<5	110	0.01	1
B291257		3.05	0.02	3.20	0.90	1575	1	0.10	13	570	97	0.86	27	142	0.22	40
B291258		2.60	<0.01	3.45	0.93	338	<1	1.40	17	640	34	0.18	12	400	0.28	42
B291259		2.66	<0.01	4.19	0.91	247	2	1.55	14	590	24	0.30	<5	485	0.28	40
B291260		2.37	<0.01	3.76	0.84	277	1	1.80	15	620	25	0.13	<5	556	0.28	40
B291261		2.28	<0.01	3.57	0.72	250	1	1.74	18	620	21	0.17	<5	517	0.29	36
B291262		2.22	<0.01	3.53	0.73	246	4	1.72	18	590	25	0.14	<5	516	0.28	35
B291263		2.68	<0.01	3.98	0.93	237	1	1.71	19	650	27	0.25	<5	554	0.31	41
B291264		2.45	<0.01	3.71	0.82	229	<1	1.79	19	630	28	0.16	<5	549	0.29	41
B291265		2.32	<0.01	3.63	0.84	231	1	1.76	19	630	28	0.10	9	518	0.29	36
B291266		2.35	<0.01	3.77	0.86	213	4	1.68	15	600	28	0.18	<5	521	0.27	35
B291267		2.43	<0.01	4.16	0.85	180	2	1.63	20	590	26	0.31	<5	497	0.27	38
B291268		2.27	<0.01	4.20	0.78	207	3	1.62	17	590	29	0.24	<5	480	0.27	36
B291269																
B291270		3.74	0.03	2.67	0.34	87	3	0.11	19	300	24	0.02	109	91	0.20	85
B291271		2.05	0.01	3.42	0.87	402	1	0.73	18	580	35	0.43	8	252	0.25	36
B291272		3.42	0.02	2.45	1.67	1575	2	0.03	8	400	1070	2.27	284	144	0.16	27
B291273		2.05	<0.01	3.54	0.73	421	1	0.49	16	550	43	0.62	10	191	0.25	38

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291234		30	552
B291235		30	153
B291236		<10	11
B291237		20	353
B291238		40	98
B291239		30	31
B291240		20	88
B291241		20	78
B291242		20	71
B291243		60	30
B291244		220	31
B291245		30	33
B291246		20	34
B291247		30	48
B291248		30	39
B291249			
B291250		<10	48
B291251		40	40
B291252		20	84
B291253		30	97
B291254		70	168
B291255		40	39
B291256		<10	7
B291257		40	251
B291258		10	64
B291259		40	36
B291260		10	51
B291261		30	48
B291262		60	47
B291263		30	42
B291264		20	45
B291265		30	50
B291266		20	39
B291267		30	26
B291268		20	29
B291269			
B291270		10	44
B291271		20	72
B291272		20	205
B291273		10	68

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291274		4.62	0.922			<0.5	8.04	98	1400	3.3	15	2.37	<0.5	8	103	41
B291275		4.46	0.442			<0.5	7.77	22	1370	2.8	12	2.28	<0.5	7	110	26
B291276		2.12	<0.005			<0.5	0.14	<5	20	<0.5	<2	19.85	<0.5	<1	8	2
B291277		1.78	0.807	1.410	1.025	<0.5	7.24	83	1360	2.9	15	2.61	<0.5	7	112	34
B291278		6.66	0.137			<0.5	8.04	26	1250	3.3	5	2.92	<0.5	7	94	23
B291279		1.86	0.094			<0.5	8.04	45	1320	3.2	2	2.79	<0.5	12	111	22
B291280		5.62	0.261			<0.5	7.29	21	1500	2.9	3	2.38	<0.5	6	96	35
B291281		2.48	0.228			<0.5	7.85	165	1450	3.0	5	3.77	<0.5	9	103	29
B291282		2.62	0.206			<0.5	7.63	374	1420	2.9	3	3.87	<0.5	9	90	27
B291283		6.06	0.797			<0.5	7.31	26	1210	3.0	12	2.71	<0.5	6	77	25
B291284		2.66	0.053			<0.5	7.64	70	1440	3.0	<2	2.92	<0.5	8	118	37
B291285		0.48	0.039			<0.5	7.68	42	1550	3.0	<2	3.15	<0.5	6	94	33
B291286		5.98	0.175			<0.5	7.98	40	1530	3.2	13	2.70	<0.5	6	122	41
B291287		5.92	1.050			<0.5	7.39	59	1430	2.8	23	2.72	<0.5	7	98	35
B291288		5.16	0.610			<0.5	8.05	41	1500	3.1	6	2.55	<0.5	7	114	60
B291289		0.04	0.415													
B291290		0.10	0.833			2.5	7.64	6	470	0.7	<2	2.00	0.9	23	101	2070
B291291		4.82	0.555			<0.5	7.77	48	1560	2.9	14	2.46	<0.5	8	107	31
B291292		3.20	0.214			<0.5	7.59	51	1590	2.9	4	2.72	<0.5	7	110	35
B291293		8.02	1.210			3.2	7.46	145	1110	2.7	17	2.95	2.3	8	102	68
B291294		6.18	3.54			<0.5	7.21	862	1550	3.0	27	2.66	<0.5	8	112	27
B291295		5.94	1.280			<0.5	7.69	578	1430	3.1	12	2.66	<0.5	7	113	33
B291296		2.38	0.006			<0.5	0.13	<5	20	<0.5	<2	19.50	<0.5	<1	6	2
B291297		6.50	0.092			<0.5	7.99	282	1650	3.0	14	2.81	<0.5	9	97	32
B291298		2.54	0.049			<0.5	8.24	153	1650	3.2	<2	2.77	<0.5	9	110	38

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291274		2.37	<0.01	3.89	0.79	269	3	1.84	16	600	30	0.20	<5	511	0.27	37
B291275		2.40	<0.01	3.80	0.82	277	2	1.76	17	580	28	0.11	6	529	0.27	41
B291276		0.12	<0.01	0.04	11.35	151	<1	0.02	8	470	<2	<0.01	<5	115	0.01	2
B291277		2.53	<0.01	3.75	1.04	348	4	1.77	18	700	22	0.16	<5	617	0.30	44
B291278		2.65	<0.01	3.59	1.14	358	2	1.90	14	740	22	0.11	<5	606	0.32	49
B291279		2.82	<0.01	3.43	1.05	377	1	1.91	13	780	22	0.11	<5	595	0.35	51
B291280		2.46	<0.01	3.36	0.94	279	8	1.77	19	650	21	0.15	5	571	0.30	40
B291281		2.66	<0.01	3.45	1.10	441	1	1.88	18	730	26	0.08	<5	622	0.32	46
B291282		2.54	<0.01	3.41	1.08	431	1	1.82	19	700	25	0.10	5	606	0.31	44
B291283		2.60	<0.01	3.51	1.18	355	2	1.88	13	660	26	0.08	9	558	0.29	45
B291284		2.67	<0.01	3.44	0.95	347	1	1.83	24	630	26	0.12	7	603	0.30	46
B291285		2.71	<0.01	3.52	1.30	411	2	1.86	17	660	22	0.06	6	690	0.31	45
B291286		2.60	<0.01	3.72	0.92	274	5	1.92	18	660	23	0.20	<5	603	0.31	44
B291287		2.63	<0.01	3.63	1.20	328	3	1.71	20	600	26	0.20	<5	551	0.28	41
B291288		2.65	<0.01	4.27	0.98	292	2	1.86	16	640	29	0.27	<5	566	0.30	45
B291289																
B291290		5.34	<0.01	1.82	1.36	447	3	3.30	51	670	18	0.63	5	219	0.30	90
B291291		2.68	<0.01	3.87	1.05	306	2	1.70	14	650	28	0.16	<5	529	0.30	45
B291292		2.72	<0.01	3.70	1.04	324	2	1.73	19	680	30	0.20	<5	547	0.31	44
B291293		2.92	0.02	3.46	0.87	576	2	0.73	15	670	281	0.67	46	308	0.28	44
B291294		2.80	<0.01	3.87	1.00	343	3	1.81	18	700	50	0.19	9	556	0.31	47
B291295		2.68	<0.01	3.65	0.98	324	6	1.62	16	620	41	0.22	9	498	0.29	45
B291296		0.12	<0.01	0.04	11.15	147	<1	0.02	3	440	<2	<0.01	<5	117	0.01	2
B291297		2.85	<0.01	3.75	1.13	342	1	1.78	15	720	45	0.21	5	580	0.31	50
B291298		2.70	0.01	3.60	1.06	345	2	1.77	15	730	32	0.18	<5	563	0.32	48

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 17-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045435

Sample Description	Method	ME-ICP61	ME-ICP61
	Analyte	W	Zn
	Units	ppm	ppm
	LOR	10	2
B291274		30	42
B291275		20	41
B291276		10	7
B291277		10	45
B291278		10	47
B291279		<10	53
B291280		10	43
B291281		10	61
B291282		10	59
B291283		20	46
B291284		10	49
B291285		10	43
B291286		40	37
B291287		10	42
B291288		20	41
B291289			
B291290		<10	209
B291291		40	47
B291292		20	58
B291293		50	362
B291294		40	54
B291295		30	67
B291296		<10	7
B291297		10	49
B291298		10	65

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da .3-JUN-2005
Account: STRGOL

CERTIFICATE VA05045437

Project: Dublin Gulch-1735

P.O. No.:

This report is for 181 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 9-JUN-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Ag-AA62	Ore grade Ag - four acid /AAS	AAS



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291299		3.02	0.021			<0.5	8.11	367	1590	3.2	<2	1.70	<0.5	5	42	15
B291300		3.26	5.38			1.2	7.82	1060	1610	2.8	62	1.22	<0.5	9	42	68
B291301		1.32	0.241			<0.5	8.38	582	1710	3.1	6	1.51	<0.5	6	44	36
B291302		1.02	0.259			<0.5	8.31	855	1680	3.0	8	1.31	<0.5	7	44	59
B291303		2.82	0.623			<0.5	8.55	853	1760	2.9	14	1.12	<0.5	6	47	42
B291304		1.54	1.280			0.5	8.82	1345	1930	3.1	22	1.26	<0.5	9	47	76
B291305		2.48	0.475			<0.5	7.85	301	1560	3.1	11	1.91	<0.5	6	44	33
B291306		3.54	0.293	0.250		<0.5	8.69	421	1770	3.1	3	2.14	<0.5	8	45	48
B291307		3.54	0.160	0.167		<0.5	8.11	330	1370	3.2	6	1.74	<0.5	7	42	28
B291308		0.80	0.290	0.292		<0.5	8.06	317	1610	3.1	7	1.80	<0.5	4	46	33
B291309		0.04	0.266	0.344												
B291310		0.10	0.087			<0.5	7.16	111	590	2.7	<2	0.53	<0.5	59	1245	415
B291311		2.74	0.372			<0.5	8.13	326	1710	3.0	12	2.01	<0.5	7	48	40
B291312		2.36	0.179			<0.5	8.43	307	1680	3.1	<2	2.02	<0.5	7	43	33
B291313		1.98	0.194			<0.5	8.37	548	1720	3.0	6	1.71	<0.5	9	45	35
B291314		1.44	0.100	0.090		<0.5	8.72	432	1800	3.3	2	2.38	<0.5	9	48	42
B291315		4.32	0.172	0.102		<0.5	8.06	291	1540	3.0	<2	2.03	<0.5	6	43	27
B291316		1.42	<0.005			<0.5	0.14	<5	20	<0.5	<2	19.00	<0.5	<1	4	2
B291317		5.60	0.146			<0.5	8.03	178	1470	3.2	<2	1.96	<0.5	4	43	35
B291318		5.40	0.144			<0.5	8.03	239	1410	2.8	<2	1.90	<0.5	8	43	39
B291319		4.96	0.276			<0.5	7.52	364	1520	2.7	5	2.35	<0.5	10	54	37
B291320		2.96	0.221			<0.5	8.51	299	1680	3.0	7	2.11	<0.5	7	43	35
B291321		1.56	0.176			<0.5	8.06	401	1590	3.0	<2	1.66	<0.5	8	43	53
B291322		1.66	1.735			<0.5	7.95	564	1600	3.1	9	1.64	<0.5	12	44	58
B291323		5.86	0.350			<0.5	7.84	658	1160	3.7	33	1.50	<0.5	10	37	41
B291324		4.06	2.19			<0.5	7.88	348	1510	3.1	17	1.95	<0.5	7	29	41
B291325		2.92	0.184			<0.5	7.62	425	1540	2.9	4	1.74	<0.5	8	29	52
B291326		3.20	0.615			<0.5	7.62	381	1590	2.9	24	1.92	<0.5	8	29	35
B291327		5.88	1.510			<0.5	8.06	342	1560	3.0	3	1.98	<0.5	8	49	44
B291328		3.56	2.37	3.71	3.71	7.4	7.47	294	1440	2.8	86	2.27	<0.5	7	47	25
B291329		0.04	>10.0	3.99	3.12											
B291330		0.10	2.65	2.62	NSS	<0.5	7.69	2120	750	12.8	<2	0.01	<0.5	1	147	102
B291331		3.16	0.238	0.547	0.260	<0.5	7.95	406	1530	3.1	7	2.21	<0.5	10	55	37
B291332		3.58	0.796			<0.5	7.85	232	1520	3.0	2	1.92	<0.5	7	52	35
B291333		2.80	0.111			<0.5	8.30	317	1640	3.2	<2	2.12	<0.5	8	51	33
B291334		1.92	0.177			<0.5	8.03	186	1620	3.2	3	2.07	<0.5	6	49	24
B291335		3.22	0.185	0.168		<0.5	7.89	365	1600	3.0	3	1.91	<0.5	7	48	48
B291336		1.76	<0.005			<0.5	0.13	<5	20	<0.5	<2	19.30	<0.5	1	3	1
B291337		6.00	0.603			<0.5	7.64	430	1620	2.9	11	1.91	<0.5	13	46	73
B291338		0.82	1.630			<0.5	6.50	535	1540	1.8	22	2.06	<0.5	11	39	44

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291299		2.12	0.03	3.80	0.57	196	1	1.61	18	580	23	0.01	<5	399	0.27	33
B291300		2.33	0.02	3.86	0.45	273	2	1.27	16	610	69	0.03	29	302	0.27	35
B291301		2.40	0.01	3.75	0.57	243	1	1.44	25	690	36	0.01	13	366	0.29	37
B291302		2.45	0.02	3.88	0.56	273	1	1.38	26	690	45	0.02	12	343	0.28	35
B291303		2.32	0.02	4.19	0.56	248	1	1.28	22	690	48	0.01	18	316	0.30	38
B291304		2.61	0.02	4.28	0.55	461	2	1.29	18	760	53	0.01	25	338	0.33	43
B291305		2.15	0.01	3.58	0.68	412	1	1.57	16	620	17	0.01	<5	442	0.28	34
B291306		2.65	0.01	3.88	0.85	310	1	1.72	21	710	22	0.02	7	489	0.31	39
B291307		1.97	0.01	4.20	0.63	315	<1	1.59	16	520	26	0.02	<5	395	0.24	28
B291308		2.20	0.01	3.73	0.71	205	1	1.56	19	600	23	0.01	7	430	0.28	34
B291309																
B291310		8.57	0.03	2.26	0.61	391	9	0.12	501	370	151	0.02	8	53	0.22	93
B291311		2.42	<0.01	3.75	0.78	229	1	1.65	17	650	23	0.02	<5	479	0.30	38
B291312		2.45	<0.01	3.80	0.81	272	<1	1.64	18	680	20	0.01	<5	488	0.30	38
B291313		2.56	0.01	3.65	0.77	713	1	1.53	19	670	13	0.01	12	447	0.30	36
B291314		2.78	<0.01	3.57	0.91	636	2	1.77	28	730	23	0.06	5	526	0.35	41
B291315		2.40	0.01	3.51	0.78	406	<1	1.66	21	640	20	0.01	<5	465	0.29	35
B291316		0.13	<0.01	0.03	11.65	149	<1	0.01	6	490	6	0.03	<5	108	0.01	1
B291317		2.22	0.01	3.94	0.76	218	<1	1.64	14	600	20	0.06	7	453	0.28	34
B291318		2.40	0.01	3.78	0.90	239	1	1.53	15	640	16	0.02	<5	444	0.27	39
B291319		2.73	0.01	3.54	1.00	301	1	1.53	17	660	23	0.13	<5	486	0.30	47
B291320		2.43	0.01	3.86	0.85	233	<1	1.64	18	650	17	0.03	6	476	0.30	37
B291321		2.39	0.01	3.92	0.84	194	1	1.47	16	620	15	0.01	5	404	0.28	34
B291322		2.49	0.01	3.81	0.84	199	1	1.46	19	620	20	0.01	10	396	0.29	34
B291323		1.86	<0.01	4.43	0.54	185	<1	1.47	13	440	36	0.06	7	326	0.19	23
B291324		2.32	<0.01	3.73	0.80	210	1	1.55	18	590	25	0.04	5	430	0.28	35
B291325		2.34	0.01	3.75	0.80	224	1	1.43	20	580	20	0.01	6	401	0.29	37
B291326		2.36	0.01	3.70	0.86	233	2	1.38	19	590	23	0.01	<5	402	0.29	36
B291327		2.48	0.01	3.69	0.87	230	1	1.52	20	620	17	0.02	<5	448	0.29	38
B291328		2.37	0.01	3.31	0.84	342	1	1.28	16	620	73	<0.01	18	377	0.27	41
B291329																
B291330		3.48	0.07	3.13	0.39	72	3	0.08	11	340	26	0.02	157	143	0.23	104
B291331		2.59	0.01	3.56	0.98	308	2	1.55	15	630	13	0.02	5	449	0.28	46
B291332		2.34	0.01	3.56	0.87	244	1	1.50	14	590	19	0.01	<5	442	0.27	40
B291333		2.50	0.01	3.64	0.90	287	<1	1.58	23	630	21	0.01	<5	465	0.30	39
B291334		2.41	0.01	3.65	0.86	269	<1	1.66	18	670	23	0.01	<5	459	0.30	37
B291335		2.33	0.02	4.08	0.77	216	1	1.57	19	630	20	0.02	7	444	0.30	38
B291336		0.12	<0.01	0.03	11.60	181	<1	0.01	9	480	6	0.02	<5	108	0.01	2
B291337		2.56	0.01	3.75	0.79	231	1	1.56	23	650	19	0.01	<5	438	0.30	38
B291338		1.56	<0.01	4.54	0.38	181	5	0.87	14	470	11	0.02	11	285	0.19	23

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	W	Zn	Ag
	Units	ppm	ppm	ppm
	LOR	10	2	1
B291299		20	50	
B291300		170	77	
B291301		210	88	
B291302		160	110	
B291303		90	71	
B291304		70	98	
B291305		30	48	
B291306		70	63	
B291307		80	48	
B291308		20	51	
B291309				
B291310		30	625	
B291311		20	59	
B291312		20	65	
B291313		30	95	
B291314		<10	77	
B291315		10	63	
B291316		10	8	
B291317		20	49	
B291318		20	59	
B291319		30	52	
B291320		30	60	
B291321		40	53	
B291322		60	52	
B291323		130	33	
B291324		100	41	
B291325		50	69	
B291326		30	46	
B291327		30	45	
B291328		30	95	
B291329				
B291330		20	16	
B291331		20	44	
B291332		30	48	
B291333		30	71	
B291334		10	63	
B291335		40	57	
B291336		10	7	
B291337		80	64	
B291338		30	68	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291339		2.78	0.406			<0.5	7.31	428	1320	2.7	4	2.07	<0.5	11	40	39
B291340		3.24	0.449			<0.5	7.48	220	1340	2.8	11	1.80	<0.5	7	42	29
B291341		0.94	0.682			<0.5	7.72	165	1600	2.8	31	2.07	<0.5	7	46	28
B291342		0.88	0.168			<0.5	8.17	177	1680	2.9	7	2.19	<0.5	9	46	22
B291343		2.22	0.040			<0.5	7.65	224	1550	2.9	<2	1.82	<0.5	10	45	58
B291344		3.80	0.624			<0.5	8.18	202	1690	2.9	25	2.25	<0.5	9	47	31
B291345		0.96	0.877			<0.5	7.63	284	1660	2.7	4	1.98	<0.5	10	48	44
B291346		3.16	0.430			<0.5	6.46	116	1280	2.4	7	1.70	<0.5	6	35	25
B291347		1.52	0.334			<0.5	6.78	314	1240	2.5	3	1.32	<0.5	6	39	36
B291348		2.80	0.211			<0.5	6.81	538	1360	2.5	3	1.34	<0.5	5	38	32
B291349		0.04	0.200													
B291350		0.10	4.47			6.0	6.07	6	360	0.7	<2	2.08	1.1	14	16	91
B291351		4.28	0.416			<0.5	6.39	562	1000	2.4	<2	1.12	<0.5	8	23	41
B291352		3.14	0.088			0.5	5.94	753	560	2.3	<2	1.86	1.3	3	16	26
B291353		1.26	0.061			<0.5	6.72	2880	840	3.1	<2	4.02	2.4	7	19	54
B291354		5.04	0.194			1.2	7.19	730	1000	3.3	<2	2.21	3.6	3	25	40
B291355		2.20	0.107			<0.5	8.19	602	920	3.4	<2	2.38	0.7	8	28	38
B291356		1.66	0.022			<0.5	0.12	15	10	<0.5	<2	19.80	<0.5	<1	2	1
B291357		3.80	0.281			1.7	7.89	197	1630	3.0	7	2.00	<0.5	4	29	36
B291358		4.34	0.115			0.7	7.56	68	1560	3.1	7	2.25	<0.5	7	28	34
B291359		4.04	0.087			<0.5	8.21	146	1700	3.1	<2	2.45	<0.5	8	31	33
B291360		5.58	0.159			<0.5	8.08	152	1590	3.1	3	2.22	<0.5	7	30	40
B291361		3.02	0.324			1.3	7.08	174	1460	2.8	9	2.03	<0.5	12	126	70
B291362		2.92	0.207			<0.5	7.64	167	1550	2.9	<2	2.11	<0.5	7	380	29
B291363		6.14	0.339			0.5	6.76	356	1300	2.8	4	1.60	<0.5	6	122	48
B291364		4.74	1.095			<0.5	7.37	525	1470	2.8	7	1.94	<0.5	11	28	45
B291365		2.78	0.660			<0.5	7.67	505	1510	2.8	10	1.84	<0.5	7	116	35
B291366		1.70	0.708			<0.5	7.62	486	1530	2.7	4	1.95	<0.5	9	28	29
B291367		1.86	0.230			<0.5	7.78	312	1460	3.3	3	1.85	<0.5	8	26	23
B291368		5.76	0.101			<0.5	7.58	462	1600	3.1	<2	2.22	<0.5	6	108	31
B291369		0.04	0.140													
B291370		0.10	3.03			<0.5	6.88	16	2020	3.1	<2	4.63	<0.5	23	135	100
B291371		4.12	0.389	0.446		<0.5	7.58	404	1540	2.8	21	2.10	<0.5	7	29	43
B291372		3.14	0.771	0.946	1.595	<0.5	8.05	905	1610	3.0	34	2.14	<0.5	19	30	75
B291373		6.24	0.458	0.156	0.108	<0.5	8.13	333	1700	2.9	7	2.30	<0.5	8	98	40
B291374		4.46	0.122			<0.5	7.56	244	1630	2.8	<2	2.17	<0.5	8	55	28
B291375		5.42	0.296			<0.5	7.72	352	1430	3.0	4	1.98	<0.5	7	27	22
B291376		1.86	0.016			<0.5	0.13	6	20	<0.5	<2	19.60	<0.5	<1	4	3
B291377		2.90	0.167			<0.5	7.47	797	1660	2.9	2	2.26	0.6	8	30	35
B291378		2.12	0.589			>100	7.67	255	1530	3.3	4	2.16	<0.5	11	48	447

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291339		2.06	0.01	4.00	0.60	215	1	1.27	14	530	21	0.01	9	327	0.24	31
B291340		2.04	0.01	3.74	0.63	211	1	1.41	20	550	22	0.01	10	364	0.24	30
B291341		2.32	0.01	3.34	0.77	282	1	1.58	19	650	22	0.01	<5	461	0.30	37
B291342		2.53	0.01	3.35	0.84	310	<1	1.62	22	680	13	0.01	<5	488	0.32	40
B291343		2.36	0.01	3.65	0.76	194	1	1.50	22	590	20	0.01	<5	421	0.28	35
B291344		2.48	<0.01	3.66	0.85	256	1	1.67	23	700	12	0.07	<5	512	0.32	40
B291345		2.45	0.01	3.49	0.79	288	1	1.46	17	660	22	0.01	9	435	0.31	39
B291346		1.86	0.01	2.90	0.63	178	<1	1.26	20	500	17	0.06	<5	368	0.23	30
B291347		2.19	0.02	2.79	0.51	246	1	0.97	19	480	40	0.01	21	265	0.24	30
B291348		2.10	0.02	3.00	0.44	244	2	0.97	18	570	46	0.02	29	238	0.26	34
B291349																
B291350		3.12	0.01	1.64	1.01	727	9	1.17	8	660	18	0.50	<5	300	0.27	109
B291351		2.12	0.02	2.83	0.32	283	3	0.59	21	530	61	0.06	32	170	0.23	30
B291352		2.16	0.07	2.48	0.23	1125	6	0.02	15	430	110	0.04	51	31	0.17	25
B291353		4.56	0.05	3.10	0.44	3830	17	0.03	32	590	150	0.01	104	77	0.20	33
B291354		2.17	0.08	3.61	0.34	1535	7	0.03	7	650	166	0.03	83	37	0.26	37
B291355		2.51	0.02	3.19	0.55	513	7	0.54	23	670	57	0.01	40	177	0.31	49
B291356		0.11	0.01	0.03	11.70	164	<1	0.01	7	530	9	0.01	<5	111	0.01	2
B291357		2.14	0.01	3.68	0.66	244	1	1.36	17	630	23	0.01	8	396	0.28	35
B291358		2.42	0.02	3.63	0.67	267	3	1.50	20	580	18	0.01	5	399	0.29	36
B291359		2.65	0.01	3.34	0.84	261	1	1.74	23	690	14	0.02	<5	495	0.33	41
B291360		2.43	0.01	3.65	0.80	248	1	1.66	21	630	20	0.05	<5	486	0.31	40
B291361		2.45	0.01	3.63	0.72	219	4	1.48	25	570	25	0.17	<5	430	0.28	37
B291362		2.56	0.01	3.39	0.77	246	3	1.57	30	630	20	0.03	<5	444	0.29	38
B291363		2.00	0.01	3.28	0.60	177	4	1.34	19	520	23	0.08	6	348	0.23	29
B291364		2.25	0.01	3.54	0.72	202	4	1.53	22	590	17	0.09	<5	412	0.27	33
B291365		2.30	<0.01	3.51	0.74	230	<1	1.56	20	600	21	0.02	9	415	0.28	36
B291366		2.35	0.01	3.39	0.73	250	2	1.52	22	620	20	0.02	14	418	0.29	35
B291367		2.22	<0.01	3.51	0.70	252	1	1.59	17	560	21	0.02	9	414	0.26	32
B291368		2.42	0.01	3.54	0.79	258	2	1.66	21	650	16	0.06	<5	492	0.31	39
B291369																
B291370		4.87	<0.01	3.19	2.87	1015	12	2.15	64	2250	27	0.29	<5	1550	0.35	160
B291371		2.26	<0.01	3.52	0.73	232	2	1.55	23	610	24	0.12	7	455	0.28	36
B291372		2.64	<0.01	3.59	0.79	244	1	1.65	24	660	27	0.27	<5	474	0.30	39
B291373		2.55	<0.01	3.62	0.85	256	1	1.65	22	680	24	0.13	<5	494	0.31	40
B291374		2.38	0.01	3.52	0.78	267	1	1.60	23	620	28	0.04	5	472	0.30	38
B291375		2.19	0.02	3.72	0.64	258	1	1.59	21	610	63	0.04	25	397	0.27	33
B291376		0.11	0.01	0.03	11.80	158	<1	0.01	13	530	6	0.01	<5	111	0.01	2
B291377		2.40	0.01	3.67	0.73	303	1	1.55	18	650	35	0.06	20	446	0.30	38
B291378		2.30	0.04	3.62	0.66	392	2	0.95	79	600	63	0.01	20	313	0.29	36

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	W	Zn	Ag
	Units	ppm	ppm	ppm
	LOR	10	2	1
B291339		20	79	
B291340		50	62	
B291341		10	66	
B291342		<10	72	
B291343		60	55	
B291344		30	51	
B291345		60	75	
B291346		40	36	
B291347		30	99	
B291348		30	114	
B291349				
B291350		<10	72	
B291351		30	129	
B291352		20	165	
B291353		30	351	
B291354		40	348	
B291355		60	265	
B291356		<10	11	
B291357		50	57	
B291358		30	46	
B291359		20	41	
B291360		50	50	
B291361		60	43	
B291362		30	43	
B291363		80	34	
B291364		150	36	
B291365		20	75	
B291366		30	98	
B291367		40	75	
B291368		20	64	
B291369				
B291370		<10	91	
B291371		50	54	
B291372		150	52	
B291373		20	56	
B291374		60	76	
B291375		20	191	
B291376		<10	11	
B291377		70	148	
B291378		1160	284	135

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291379		5.22	0.101			3.3	8.38	158	1720	2.9	<2	2.01	<0.5	8	33	39
B291380		5.56	0.375			<0.5	7.44	92	1350	3.3	7	2.10	<0.5	8	49	22
B291381		3.22	0.218			<0.5	7.68	61	1540	3.0	15	2.32	<0.5	7	30	49
B291382		3.06	0.123			<0.5	8.04	40	1530	3.1	<2	2.36	<0.5	8	59	30
B291383		6.10	0.366			<0.5	8.23	102	1600	3.2	4	2.23	<0.5	8	29	34
B291384		6.42	0.435			<0.5	7.14	97	1420	2.8	22	2.05	<0.5	8	68	41
B291385		3.24	0.126			<0.5	8.34	93	1750	3.4	<2	2.36	<0.5	7	32	43
B291386		4.36	2.07			1.0	7.49	209	1110	3.0	31	2.53	0.8	9	61	37
B291387		5.44	2.67			1.9	6.73	367	760	2.4	66	2.49	<0.5	7	24	42
B291388		8.52	0.095			2.9	7.78	98	1770	3.0	3	2.39	<0.5	8	59	27
B291389		0.04	0.100													
B291390		0.10	0.422			2.2	9.68	<5	1090	1.2	<2	1.52	<0.5	8	6	7310
B291391		6.42	0.195			<0.5	7.87	78	1720	2.9	2	2.45	<0.5	8	29	35
B291392		6.24	0.070			<0.5	8.10	69	1780	3.1	<2	2.59	<0.5	8	58	19
B291393		7.38	0.125			<0.5	8.27	72	1730	2.9	10	2.52	<0.5	7	31	26
B291394		5.98	0.259			<0.5	7.71	59	1660	2.7	2	2.35	<0.5	8	57	22
B291395		6.70	0.151			<0.5	7.75	94	1500	2.8	5	2.47	<0.5	9	29	22
B291396		1.42	<0.005			<0.5	0.14	<5	20	<0.5	<2	19.55	<0.5	<1	5	1
B291397		5.96	0.810			<0.5	8.00	78	1560	2.9	14	2.31	<0.5	8	27	32
B291398		6.38	0.442			<0.5	7.79	126	1530	3.0	16	2.24	<0.5	9	63	57
B291399		2.72	1.705			<0.5	7.25	466	1520	2.9	20	1.87	<0.5	11	123	61
B291400		1.44	0.272			<0.5	3.76	387	600	1.5	8	0.94	0.8	4	21	58
B291401		0.76	0.308			0.6	6.83	675	1080	2.5	5	1.85	1.4	7	157	38
B291402		0.90	0.609			<0.5	5.71	733	1030	2.0	5	1.33	<0.5	14	22	38
B291403		3.46	0.138			0.6	7.55	376	1120	2.7	2	2.27	3.1	7	124	43
B291404		4.70	0.389			<0.5	7.41	101	1580	3.0	2	2.24	<0.5	7	30	27
B291405		2.34	0.040			<0.5	8.06	387	1370	3.2	<2	2.31	<0.5	8	113	24
B291406		1.92	0.304			0.8	4.67	852	460	1.9	6	3.08	2.4	5	16	37
B291407		3.04	0.608			<0.5	7.10	1165	1470	2.6	9	1.14	<0.5	9	130	68
B291408		3.60	0.075			<0.5	7.82	142	1580	3.1	<2	2.02	<0.5	9	25	34
B291409		0.04	0.068													
B291410		0.10	0.436			2.3	9.37	<5	1120	1.2	<2	1.47	<0.5	9	9	7260
B291411		1.88	0.149			<0.5	7.82	146	1700	2.9	<2	1.77	<0.5	9	102	54
B291412		3.48	0.153			<0.5	7.90	126	1650	3.0	4	2.10	<0.5	10	28	44
B291413		6.12	0.192			<0.5	7.05	112	1530	2.9	2	2.40	<0.5	10	103	50
B291414		5.62	0.050			<0.5	8.22	66	1730	3.1	<2	2.36	<0.5	11	31	29
B291415		2.60	0.157			<0.5	7.85	172	1620	2.7	5	2.39	<0.5	15	110	34
B291416		1.74	<0.005			<0.5	0.14	5	20	<0.5	<2	20.9	<0.5	1	4	5
B291417		4.00	1.065			<0.5	7.52	160	1650	2.7	20	2.46	<0.5	8	105	40
B291418		5.12	0.424			<0.5	7.88	316	1060	3.1	2	2.70	1.2	10	27	40

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1
B291379		2.47	0.01	3.56	0.73	233	1	1.68	18	700	25	0.03	<5	493	0.29	37
B291380		2.09	0.01	3.71	0.63	233	<1	1.63	18	550	27	0.05	<5	425	0.25	31
B291381		2.39	<0.01	3.59	0.78	221	8	1.67	22	620	25	0.23	<5	487	0.29	36
B291382		2.42	<0.01	3.52	0.79	234	4	1.71	21	620	27	0.19	<5	500	0.29	35
B291383		2.33	0.01	3.83	0.74	197	1	1.71	20	610	24	0.15	<5	476	0.27	33
B291384		2.27	<0.01	3.52	0.71	172	3	1.50	19	550	21	0.19	<5	436	0.27	34
B291385		2.60	0.01	3.70	0.81	242	1	1.72	21	670	28	0.15	<5	501	0.31	40
B291386		2.66	0.05	3.27	0.67	687	4	0.83	20	630	1025	0.40	384	287	0.28	36
B291387		2.18	0.02	2.88	0.58	573	8	0.37	15	450	166	0.34	94	203	0.23	30
B291388		2.47	<0.01	3.77	0.80	300	1	1.74	24	660	32	0.08	<5	512	0.32	40
B291389																
B291390		3.32	0.03	3.62	1.20	490	3	3.27	16	1950	12	0.24	<5	684	0.33	174
B291391		2.43	0.01	3.65	0.78	274	1	1.64	18	640	22	0.11	<5	502	0.30	38
B291392		2.63	0.01	3.61	0.91	324	1	1.79	28	680	24	0.08	<5	561	0.34	43
B291393		2.65	0.01	3.67	0.93	297	2	1.63	23	700	28	0.11	9	494	0.32	41
B291394		2.49	0.01	3.37	0.91	275	1	1.49	22	670	23	0.09	12	445	0.31	39
B291395		2.45	0.01	3.66	0.81	310	<1	1.55	20	630	27	0.08	8	443	0.30	38
B291396		0.12	<0.01	0.04	11.45	167	<1	0.01	11	500	<2	0.01	<5	116	0.01	2
B291397		2.30	<0.01	3.84	0.73	254	4	1.56	21	630	20	0.19	6	473	0.28	34
B291398		2.34	<0.01	3.81	0.79	195	1	1.56	17	580	17	0.29	<5	463	0.28	35
B291399		2.26	0.01	3.62	0.63	185	4	1.31	25	540	34	0.35	15	400	0.26	34
B291400		1.74	0.02	1.93	0.39	222	5	0.27	6	290	21	0.44	16	104	0.12	15
B291401		2.23	0.03	3.66	0.56	501	5	0.49	16	510	106	0.12	36	201	0.24	31
B291402		1.90	0.02	3.34	0.45	295	5	0.50	12	460	38	0.14	25	192	0.20	24
B291403		2.66	0.06	3.75	0.78	579	1	0.50	19	560	171	0.27	34	218	0.26	35
B291404		2.29	0.01	3.50	0.65	261	1	1.52	19	590	28	0.11	7	432	0.28	35
B291405		2.37	0.02	3.87	0.66	406	1	1.08	20	620	48	0.18	25	343	0.29	36
B291406		2.31	0.05	1.98	1.03	763	4	0.24	8	340	476	0.17	127	170	0.16	19
B291407		1.92	0.05	3.63	0.44	149	3	1.24	19	550	41	0.06	17	327	0.26	31
B291408		2.19	0.01	3.53	0.63	237	2	1.64	18	600	26	0.08	<5	429	0.29	35
B291409																
B291410		3.26	0.03	3.64	1.17	478	2	3.42	11	1900	10	0.24	<5	689	0.34	175
B291411		2.10	0.01	4.06	0.48	209	2	1.46	17	550	27	0.09	14	392	0.27	33
B291412		2.37	0.01	3.89	0.67	213	2	1.68	22	600	25	0.14	5	465	0.30	36
B291413		2.39	0.01	3.66	0.73	273	1	1.57	21	590	43	0.24	12	445	0.29	37
B291414		2.43	0.01	3.67	0.77	273	<1	1.77	22	610	28	0.12	<5	504	0.32	40
B291415		2.48	0.02	3.88	0.61	343	1	1.42	26	660	57	0.10	19	408	0.32	41
B291416		0.12	<0.01	0.04	11.70	167	<1	0.01	<1	510	3	0.01	<5	117	<0.01	2
B291417		2.48	0.02	3.61	0.79	321	2	1.36	19	630	82	0.24	36	423	0.31	38
B291418		2.66	0.04	3.79	0.82	593	<1	0.43	21	650	80	0.28	53	256	0.30	38

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	W	Zn	Ag
	Units	ppm	ppm	ppm
	LOR	10	2	1
B291379		60	60	
B291380		20	44	
B291381		30	38	
B291382		40	40	
B291383		40	32	
B291384		40	27	
B291385		20	40	
B291386		20	176	
B291387		130	162	
B291388		70	66	
B291389				
B291390		10	66	
B291391		20	58	
B291392		20	72	
B291393		20	61	
B291394		50	59	
B291395		40	68	
B291396		<10	7	
B291397		240	48	
B291398		40	31	
B291399		100	35	
B291400		40	109	
B291401		40	256	
B291402		30	202	
B291403		30	471	
B291404		10	45	
B291405		20	116	
B291406		30	285	
B291407		40	134	
B291408		20	50	
B291409				
B291410		<10	57	
B291411		30	56	
B291412		30	39	
B291413		20	90	
B291414		20	62	
B291415		120	162	
B291416		<10	12	
B291417		70	64	
B291418		30	178	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B291419		4.16	0.151			0.7	7.17	479	780	2.8	9	3.44	4.0	10	82	40
B291420		5.38	0.650			<0.5	7.57	327	990	2.9	7	2.68	1.1	8	26	28
B291421		0.96	9.07			4.4	3.30	2120	310	1.4	204	1.06	2.4	18	137	38
B291422		0.62	>10.0			8.7	4.04	3670	390	1.7	612	1.28	3.0	29	17	87
B291423		4.16	1.920			0.8	7.91	333	1380	3.1	48	2.20	3.3	11	89	40
B291424		2.72	0.325			<0.5	8.23	51	1600	3.7	9	2.34	<0.5	9	44	17
B291425		5.50	0.031			<0.5	7.89	24	1650	3.3	<2	2.31	<0.5	8	43	28
B291426		6.14	0.019			<0.5	7.97	28	1570	3.3	<2	2.39	<0.5	9	41	21
B291427		5.98	0.026			<0.5	7.37	16	1530	3.2	<2	2.29	<0.5	8	43	22
B291428		6.58	0.297			<0.5	7.51	32	1590	3.1	3	2.41	<0.5	9	47	32
B291429		0.04	0.144													
B291430		0.10	0.077			<0.5	7.30	115	620	2.8	<2	0.53	<0.5	60	1185	407
B291431		6.24	0.057			<0.5	8.18	53	1680	3.1	<2	2.47	<0.5	9	46	30
B291432		6.72	0.049			<0.5	8.07	31	1660	3.0	<2	2.26	<0.5	8	45	38
B291433		6.36	0.060			<0.5	7.93	27	1550	3.2	2	2.44	<0.5	10	46	35
B291434		6.20	0.066			<0.5	7.99	44	1530	3.2	<2	2.33	<0.5	8	44	34
B291435		5.08	0.041			<0.5	8.43	14	1640	3.3	2	2.29	<0.5	9	43	36
B291436		1.96	<0.005			<0.5	0.15	10	20	<0.5	<2	20.8	<0.5	1	3	2
B291437		4.44	0.301			<0.5	7.90	130	1590	3.2	2	2.46	<0.5	8	43	28
B291438		6.04	0.039			<0.5	8.30	64	1750	3.3	9	2.44	<0.5	8	45	49
B291439		7.02	1.055			6.9	7.53	265	1540	2.9	113	2.87	<0.5	14	45	111
B291440		6.30	0.189			<0.5	7.86	161	1640	3.2	5	2.29	<0.5	9	44	39
B291441		3.74	0.820			<0.5	7.46	130	1520	3.1	27	1.96	<0.5	7	44	41
B291442		3.56	0.280			<0.5	7.69	132	1540	3.2	18	2.03	<0.5	8	47	44
B291443		4.74	0.096			<0.5	7.05	286	1180	2.6	3	1.87	<0.5	6	40	40
B291444		5.72	0.040			<0.5	8.38	198	1790	3.3	<2	1.68	<0.5	10	46	32
B291445		5.46	0.070			<0.5	7.59	221	1610	3.0	2	2.15	<0.5	13	39	39
B291446		5.96	0.090			<0.5	8.11	40	1680	3.2	<2	2.48	<0.5	10	44	22
B291447		6.40	0.589			<0.5	7.76	51	1640	3.1	23	2.45	<0.5	9	45	55
B291448		6.02	0.060			<0.5	7.84	42	1550	3.0	2	2.49	0.7	10	47	41
B291449		0.04	0.045													
B291450		0.12	2.83			<0.5	6.78	5	2140	3.4	<2	4.57	<0.5	27	146	98
B291451		4.70	0.125			<0.5	8.09	79	1660	3.3	7	2.11	<0.5	8	46	43
B291452		6.50	>10.0			<0.5	7.92	43	1600	3.0	94	2.43	<0.5	9	43	29
B291453		4.48	0.068			<0.5	8.01	60	1730	3.1	5	2.19	0.5	9	48	46
B291454		1.50	0.220			<0.5	6.83	57	1420	1.9	13	1.81	<0.5	9	44	73
B291455		3.14	0.094			<0.5	7.78	55	1670	3.0	3	2.14	<0.5	11	48	46
B291456		1.56	<0.005			<0.5	0.12	6	20	<0.5	<2	19.80	<0.5	1	3	2
B291457		3.40	0.093			<0.5	7.75	31	1480	2.9	<2	2.09	0.5	8	43	41
B291458		5.84	0.041			<0.5	8.38	38	1660	3.4	3	2.54	<0.5	10	46	33

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291419		2.58	0.16	3.30	0.88	698	1	0.08	16	500	379	0.19	160	170	0.23	32
B291420		2.49	0.06	3.46	0.96	545	1	0.88	16	580	69	0.18	44	248	0.27	34
B291421		2.03	0.01	1.52	0.41	289	2	0.02	10	270	2040	0.38	971	85	0.11	15
B291422		2.12	0.01	1.82	0.44	260	4	0.03	10	300	3630	0.49	2000	118	0.13	17
B291423		2.36	0.02	3.86	0.69	335	<1	1.21	20	600	230	0.27	111	349	0.27	34
B291424		2.37	0.01	3.82	0.77	308	1	1.90	20	630	42	0.08	10	478	0.30	36
B291425		2.39	<0.01	3.75	0.81	279	6	1.88	23	620	26	0.14	<5	512	0.31	38
B291426		2.34	0.01	3.77	0.75	297	1	1.85	19	610	33	0.10	6	470	0.30	36
B291427		2.26	0.06	3.61	0.74	272	<1	1.84	19	590	30	0.11	<5	482	0.29	35
B291428		2.40	0.03	3.65	0.78	316	2	1.84	23	620	36	0.12	5	485	0.31	38
B291429																
B291430		8.65	0.07	2.28	0.60	389	8	0.13	507	340	151	0.02	11	54	0.27	97
B291431		2.38	0.02	3.74	0.79	273	3	1.83	22	660	28	0.13	<5	513	0.32	39
B291432		2.39	0.02	3.81	0.72	241	1	1.85	20	640	20	0.14	<5	498	0.31	38
B291433		2.32	0.01	3.72	0.74	250	2	1.84	18	590	29	0.18	<5	499	0.30	38
B291434		2.27	0.01	3.78	0.72	233	1	1.84	19	570	23	0.17	<5	486	0.29	35
B291435		2.51	0.01	3.98	0.77	264	1	1.93	20	660	31	0.12	5	510	0.32	39
B291436		0.12	<0.01	0.03	11.80	186	<1	0.01	3	600	5	0.01	<5	118	<0.01	2
B291437		2.42	0.01	3.54	0.80	282	1	1.80	22	620	25	0.16	<5	491	0.31	38
B291438		2.51	0.01	3.83	0.84	238	3	1.74	20	630	26	0.25	<5	519	0.31	39
B291439		2.81	0.01	3.60	1.15	223	23	1.54	26	590	21	0.52	<5	448	0.28	35
B291440		2.31	0.01	3.62	0.76	200	2	1.65	16	620	19	0.22	<5	486	0.29	36
B291441		2.06	<0.01	3.83	0.65	173	3	1.48	17	540	23	0.22	<5	425	0.26	33
B291442		2.14	<0.01	4.00	0.67	180	2	1.57	18	590	20	0.25	<5	440	0.27	34
B291443		2.05	0.01	3.11	0.73	256	2	1.32	15	550	24	0.11	8	306	0.25	33
B291444		2.78	0.05	3.72	0.76	206	2	1.66	22	670	25	0.08	<5	466	0.32	41
B291445		2.20	0.02	3.66	0.69	214	4	1.62	22	560	18	0.19	<5	457	0.29	36
B291446		2.42	0.01	3.59	0.80	285	2	1.72	18	630	23	0.11	<5	509	0.31	39
B291447		2.47	0.01	3.85	0.78	264	2	1.66	21	600	24	0.30	8	477	0.30	37
B291448		2.25	0.02	3.53	0.65	307	3	1.38	20	580	56	0.19	21	431	0.29	36
B291449																
B291450		4.88	0.01	3.44	2.83	1010	13	2.19	67	2240	24	0.29	<5	1585	0.37	169
B291451		2.31	0.01	4.00	0.75	205	2	1.64	20	600	23	0.07	<5	492	0.30	37
B291452		2.31	<0.01	3.78	0.80	246	2	1.59	16	620	27	0.14	<5	482	0.29	36
B291453		2.41	0.01	4.36	0.86	250	14	1.59	22	630	20	0.21	<5	487	0.31	37
B291454		2.05	0.01	5.08	0.73	208	67	0.99	17	460	16	0.38	<5	354	0.19	26
B291455		2.52	0.01	3.81	0.84	306	5	1.58	20	660	47	0.25	7	456	0.32	41
B291456		0.12	<0.01	0.03	11.55	162	<1	0.01	1	470	<2	0.01	<5	115	<0.01	2
B291457		2.19	<0.01	3.88	0.73	226	6	1.56	17	570	31	0.18	<5	457	0.27	34
B291458		2.42	<0.01	3.76	0.84	274	2	1.78	21	630	22	0.16	<5	522	0.32	40

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2	Ag-AA62 Ag ppm 1
B291419		20	573	
B291420		20	208	
B291421		30	290	
B291422		40	229	
B291423		40	734	
B291424		<10	116	
B291425		20	55	
B291426		10	64	
B291427		20	55	
B291428		10	71	
B291429				
B291430		30	630	
B291431		70	59	
B291432		30	49	
B291433		520	49	
B291434		80	43	
B291435		30	54	
B291436		<10	7	
B291437		10	59	
B291438		60	41	
B291439		80	30	
B291440		30	31	
B291441		40	29	
B291442		40	28	
B291443		20	43	
B291444		10	52	
B291445		20	36	
B291446		10	50	
B291447		40	43	
B291448		30	112	
B291449				
B291450		<10	97	
B291451		20	33	
B291452		30	42	
B291453		40	44	
B291454		90	21	
B291455		40	92	
B291456		<10	8	
B291457		50	56	
B291458		20	53	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	WEI-21	Au-AA23	Au-AA23	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Recvd Wt.	Au	Au Check	Au Check	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu
	Units	kg	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
	LOR	0.02	0.005	0.005	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1
B291459		3.92	0.017			<0.5	8.00	168	1690	3.3	2	2.64	<0.5	10	56	32
B291460		2.94	0.052			<0.5	8.30	67	1710	3.1	5	2.66	<0.5	8	45	40
B291461		3.18	0.019			<0.5	8.48	245	1770	3.3	<2	2.36	<0.5	9	50	15
B291462		3.28	0.024			<0.5	8.04	491	1800	3.1	<2	2.26	<0.5	11	51	26
B291463		7.36	0.047			<0.5	7.33	66	1500	2.9	<2	2.78	<0.5	7	45	26
B291464		3.72	0.072			<0.5	8.27	54	1710	3.2	7	2.93	<0.5	10	57	46
B291465		1.66	0.063			20.1	8.08	208	1910	3.1	4	2.04	<0.5	8	71	71
B291466		4.42	0.103			<0.5	8.52	26	1870	3.2	<2	2.72	<0.5	11	51	34
B291467		5.80	0.045			<0.5	8.57	25	1780	3.0	6	2.64	<0.5	10	49	27
B291468		4.36	0.628			<0.5	7.99	66	1570	2.9	37	2.81	<0.5	10	44	75
B291469		0.04	0.717													
B291470		0.10	0.081			<0.5	7.24	116	660	2.8	2	0.55	0.5	62	1295	421
B291471		4.84	0.025			<0.5	8.46	42	1760	3.1	<2	2.57	<0.5	9	48	26
B291472		5.10	0.020			<0.5	7.82	34	1560	2.9	<2	2.40	<0.5	10	45	42
B291473		3.60	0.039			1.0	7.61	39	960	2.8	6	3.68	2.0	8	40	60
B291474		2.82	0.022			<0.5	8.24	74	1940	2.9	3	1.84	<0.5	12	46	35
B291475		3.36	0.054			<0.5	7.64	61	1630	3.0	4	2.54	0.8	10	46	56
B291476		1.78	<0.005			<0.5	0.12	7	20	<0.5	<2	19.45	<0.5	<1	4	2
B291477		4.40	0.294			<0.5	7.28	26	1550	2.8	10	2.02	<0.5	9	39	57
B291478		3.98	0.156			<0.5	6.66	45	1260	2.6	8	2.72	<0.5	7	36	46
B291479		5.48	0.155			<0.5	7.13	128	1430	3.0	2	1.72	<0.5	9	42	51

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B291459		2.51	<0.01	3.71	0.82	309	1	1.73	27	640	31	0.15	<5	510	0.32	40
B291460		2.44	<0.01	4.12	0.82	302	6	1.63	19	630	30	0.19	<5	493	0.31	39
B291461		2.44	0.01	3.62	0.86	291	1	1.81	23	660	31	0.10	<5	530	0.33	41
B291462		2.39	0.01	3.64	0.83	273	1	1.78	25	660	28	0.14	<5	520	0.33	41
B291463		2.33	0.01	3.53	1.12	298	<1	1.46	16	570	18	0.15	<5	493	0.28	35
B291464		2.80	<0.01	3.54	0.95	316	2	1.65	22	660	21	0.21	<5	526	0.32	44
B291465		2.62	0.01	3.66	0.74	277	9	1.42	30	610	28	0.08	9	403	0.30	37
B291466		2.68	<0.01	3.75	0.86	324	3	1.85	20	720	21	0.14	<5	573	0.35	44
B291467		2.61	<0.01	3.48	0.87	309	5	1.72	24	650	30	0.13	<5	528	0.33	44
B291468		2.53	0.01	3.49	0.75	301	5	1.48	22	640	41	0.29	14	441	0.31	39
B291469																
B291470		8.86	0.03	2.33	0.62	402	10	0.13	506	370	154	0.03	16	56	0.22	100
B291471		2.48	0.01	3.56	0.70	295	2	1.68	23	660	20	0.16	5	500	0.32	40
B291472		2.60	0.01	3.94	0.84	399	1	1.12	23	630	51	0.39	20	355	0.31	40
B291473		2.53	0.04	3.54	1.26	808	5	0.26	17	610	161	0.28	52	226	0.26	35
B291474		2.59	0.01	3.92	0.74	266	3	1.06	30	680	26	0.35	21	312	0.32	40
B291475		2.79	0.01	3.53	1.00	402	4	0.93	22	630	72	0.36	22	325	0.29	39
B291476		0.11	<0.01	0.04	11.15	146	<1	0.01	1	500	2	0.01	<5	111	<0.01	2
B291477		2.12	0.01	3.69	0.69	224	3	1.29	16	550	60	0.31	15	355	0.26	33
B291478		2.28	<0.01	3.47	0.91	418	2	1.13	17	530	60	0.26	12	337	0.25	31
B291479		2.09	0.01	3.61	0.69	224	2	1.26	19	580	37	0.25	12	326	0.28	34

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045437

Sample Description	Method	ME-ICP61	ME-ICP61	Ag-AA62
	Analyte	W	Zn	Ag
	Units	ppm	ppm	ppm
	LOR	10	2	1
B291459		40	64	
B291460		80	60	
B291461		10	67	
B291462		10	64	
B291463		20	46	
B291464		10	52	
B291465		130	65	
B291466		10	73	
B291467		10	66	
B291468		30	44	
B291469				
B291470		30	646	
B291471		10	52	
B291472		10	93	
B291473		20	333	
B291474		20	123	
B291475		20	132	
B291476		<10	8	
B291477		10	48	
B291478		20	39	
B291479		10	50	

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 2-JUN-2005
Account: STRGOL

CERTIFICATE VA05045519

Project: Dublin Gulch-1735

P.O. No.:

This report is for 20 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 13-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 22-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045519

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291480		4.22	<0.005	<0.5	5.68	247	570	1.3	<2	0.16	1.0	7	96	20	2.26	0.01
B291481		0.62	0.005	<0.5	10.15	218	1120	2.6	3	0.13	<0.5	14	116	30	3.74	0.01
B291482		0.54	0.014	<0.5	10.70	306	1080	2.7	2	0.15	0.6	16	135	42	4.58	0.01
B291483		1.96	0.027	<0.5	10.30	331	1190	2.5	4	0.27	<0.5	13	79	26	3.65	<0.01
B291484		4.32	0.041	<0.5	10.55	183	1150	2.7	4	0.23	0.6	16	117	29	4.17	<0.01
B291485		2.50	0.019	<0.5	10.35	166	1150	2.5	2	0.28	<0.5	12	88	22	3.70	0.10
B291486		2.64	0.060	<0.5	7.15	323	1510	2.9	3	1.99	<0.5	6	60	24	2.21	0.01
B291487		1.64	0.226	<0.5	8.84	271	1280	2.4	152	1.01	<0.5	9	57	20	2.92	0.01
B291488		2.16	0.376	<0.5	7.63	431	1720	2.9	21	2.24	<0.5	10	52	25	2.36	0.01
B291489		0.04	0.478													
B291490		0.10	0.239	2.6	9.46	6	1100	1.2	5	1.58	<0.5	8	12	7720	3.41	0.02
B291491		3.66	0.972	<0.5	6.86	482	1460	2.6	10	2.26	<0.5	7	22	45	2.11	0.01
B291492		2.32	0.281	<0.5	6.95	699	1570	2.5	18	1.60	<0.5	8	48	50	2.12	0.01
B291493		2.16	0.470	<0.5	7.48	571	1610	2.8	11	1.44	<0.5	8	26	44	2.16	0.01
B291494		3.02	0.114	<0.5	7.08	463	1580	2.9	7	1.93	<0.5	9	52	40	2.38	0.01
B291495		2.26	<0.005	<0.5	7.15	279	1460	2.9	5	1.94	<0.5	7	28	32	2.25	0.01
B291496		1.24	0.396	<0.5	0.10	6	30	<0.5	<2	19.65	<0.5	<1	4	4	0.10	<0.01
B291497		4.10	0.843	<0.5	7.30	645	1540	3.0	17	2.05	<0.5	10	28	72	2.46	0.01
B291498		4.20	0.636	<0.5	6.43	1200	1340	2.4	30	1.99	<0.5	10	46	70	2.08	0.03
B291499		5.88	0.779	<0.5	7.24	1195	1530	3.0	33	1.85	<0.5	9	26	70	2.38	0.02

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 22-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05045519

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291480		2.63	0.29	149	3	0.58	19	220	10	0.01	17	56	0.20	53	20	368
B291481		4.30	0.61	115	2	0.55	34	270	8	<0.01	5	87	0.63	159	10	197
B291482		4.54	0.71	145	4	0.55	40	290	5	<0.01	10	91	0.60	159	<10	212
B291483		4.78	0.74	215	1	0.77	32	360	13	0.01	18	117	0.44	96	<10	167
B291484		4.72	0.88	252	4	0.56	43	240	14	0.02	6	124	0.53	114	<10	150
B291485		5.07	0.81	238	2	0.69	31	270	16	0.01	5	140	0.45	98	10	122
B291486		3.44	0.75	213	1	1.57	20	610	19	0.02	<5	424	0.29	36	10	94
B291487		4.04	0.78	224	1	1.04	25	890	19	0.01	<5	238	0.38	70	10	102
B291488		3.75	0.79	239	1	1.34	19	660	17	<0.01	5	400	0.30	38	30	70
B291489																
B291490		3.82	1.18	493	3	3.51	11	1990	10	0.24	<5	718	0.34	173	<10	59
B291491		3.93	0.63	186	1	1.26	18	610	19	0.02	<5	348	0.28	34	30	83
B291492		3.69	0.67	158	2	1.04	19	630	21	0.01	7	301	0.29	35	70	48
B291493		3.97	0.63	158	1	1.26	20	640	19	<0.01	7	330	0.29	36	30	82
B291494		3.77	0.82	291	2	1.52	21	640	22	0.01	<5	415	0.29	37	60	62
B291495		3.78	0.75	219	1	1.50	20	580	22	<0.01	5	388	0.28	34	20	48
B291496		0.03	10.95	136	<1	0.01	6	490	4	0.01	<5	111	<0.01	1	<10	8
B291497		3.58	0.78	216	1	1.52	24	650	20	0.01	<5	415	0.30	37	180	35
B291498		3.90	0.68	149	2	0.91	16	560	17	0.02	<5	299	0.24	31	30	20
B291499		3.73	0.80	165	2	1.25	20	600	19	0.02	<5	356	0.29	37	30	29

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Dat 3-JUN-2005
Account: STRGOL

CERTIFICATE VA05044876


Project: Dublin Gulch-1735

P.O. No.:

This report is for 111 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 13-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	



SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291500		6.36	0.184	<0.5	7.86	863	1690	2.9	17	1.96	<0.5	9	46	57	2.63	0.02
B291501		2.22	0.886	<0.5	7.51	736	1480	2.6	13	2.12	<0.5	9	67	57	2.40	0.01
B291502		2.40	0.234	<0.5	7.76	966	1360	2.6	7	2.31	<0.5	8	66	56	2.39	0.01
B291503		3.18	0.248	<0.5	7.90	900	1510	2.5	12	1.41	<0.5	11	44	33	2.40	0.01
B291504		2.78	0.134	<0.5	7.36	550	1510	2.7	8	2.09	<0.5	9	77	54	2.44	0.02
B291505		6.22	0.117	<0.5	6.85	439	1500	2.6	4	2.02	<0.5	7	42	45	2.30	0.01
B291506		6.26	0.302	<0.5	6.62	736	1360	2.6	9	2.11	<0.5	10	72	49	2.20	0.01
B291507		5.30	0.156	<0.5	7.80	280	1440	3.4	15	2.13	<0.5	9	44	23	2.31	0.01
B291508		6.10	0.768	<0.5	6.93	445	1580	2.9	24	2.37	<0.5	9	68	48	2.35	0.02
B291509		<0.02	4.17													
B291510		0.10	0.091	<0.5	7.47	119	610	2.8	2	0.55	<0.5	64	1255	423	9.09	0.04
B291511		5.18	0.221	<0.5	6.73	401	1500	2.7	35	2.86	<0.5	8	39	35	2.10	0.03
B291512		5.28	0.128	<0.5	6.77	401	1450	2.6	3	2.56	<0.5	9	71	42	2.12	0.03
B291513		5.10	0.263	<0.5	7.21	572	1660	2.5	<2	2.45	<0.5	8	37	35	2.20	0.03
B291514		5.08	0.571	<0.5	7.03	915	1500	2.8	6	2.00	<0.5	8	72	29	2.19	0.03
B291515		4.20	0.111	<0.5	6.90	819	1280	2.6	4	3.46	<0.5	7	33	24	2.52	0.04
B291516		1.62	<0.005	<0.5	0.10	<5	10	<0.5	<2	19.65	<0.5	1	6	1	0.10	<0.01
B291517		3.82	0.358	0.6	6.23	660	880	2.3	7	2.44	<0.5	10	40	58	2.36	0.03
B291518		0.46	0.166	<0.5	1.12	823	60	<0.5	7	1.27	<0.5	8	127	63	2.01	0.01
B291519		1.98	1.210	<0.5	9.68	1170	830	3.6	42	2.75	<0.5	50	23	236	8.00	0.02
B291520		2.36	0.060	<0.5	8.08	622	1540	2.6	<2	1.28	<0.5	11	42	30	2.75	0.02
B291521		3.30	0.092	<0.5	7.52	663	1840	2.7	<2	2.54	<0.5	8	62	23	2.43	0.02
B291522		3.10	0.087	<0.5	7.28	996	1710	2.8	2	2.17	<0.5	8	36	25	2.35	0.04
B291523		5.02	0.118	<0.5	8.32	649	1800	3.0	<2	2.24	<0.5	7	73	40	2.66	0.04
B291524		5.60	0.153	<0.5	7.64	702	1700	3.1	11	2.22	<0.5	9	42	48	2.43	0.04
B291525		6.22	0.599	<0.5	7.59	542	1760	2.9	11	1.97	<0.5	6	42	37	2.35	0.03
B291526		4.68	0.251	<0.5	7.61	954	1630	3.0	9	2.18	<0.5	7	39	57	2.36	0.03
B291527		3.18	0.199	<0.5	7.28	720	1800	2.8	7	2.30	<0.5	6	44	39	2.46	0.02
B291528		2.12	0.066	<0.5	7.30	300	1580	3.2	<2	2.23	<0.5	7	36	33	2.47	0.02
B291529		<0.02	0.124													
B291530		0.12	0.844	2.4	7.48	7	470	0.7	<2	1.85	0.8	20	99	1975	5.00	0.01
B291531		6.66	0.297	<0.5	7.30	1015	1740	2.9	8	1.74	<0.5	6	43	40	2.23	0.02
B291532		6.56	0.434	<0.5	7.07	1770	1600	2.7	11	2.16	<0.5	9	40	77	2.47	0.02
B291533		5.74	0.326	0.7	7.16	950	1550	2.7	13	1.81	<0.5	6	37	48	2.16	0.02
B291534		3.02	0.349	<0.5	7.89	767	1590	2.7	8	2.79	<0.5	7	37	55	2.44	0.01
B291535		3.56	0.094	0.5	6.78	151	1640	2.7	2	2.70	<0.5	6	40	34	2.40	0.01
B291536		1.42	<0.005	<0.5	0.18	11	30	<0.5	<2	20.3	<0.5	<1	4	2	0.14	<0.01
B291537		4.30	0.070	<0.5	7.41	21	1430	3.0	<2	1.85	<0.5	5	39	16	2.06	0.02
B291538		5.94	0.276	<0.5	7.13	52	1720	2.8	10	2.23	<0.5	7	36	28	2.43	0.01
B291539		5.38	0.051	<0.5	7.51	31	1800	3.0	<2	2.57	<0.5	9	41	23	2.51	0.01

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291500		3.70	0.85	203	1	1.54	21	700	15	0.03	<5	427	0.31	42	20	37
B291501		3.86	0.79	213	3	1.35	20	670	15	0.01	5	351	0.29	37	50	48
B291502		3.81	0.80	209	3	1.33	19	650	14	0.02	<5	366	0.28	36	40	38
B291503		3.81	0.77	201	2	1.20	22	670	15	0.02	7	305	0.30	38	20	42
B291504		3.61	0.77	211	4	1.20	21	620	11	0.01	<5	383	0.28	37	20	66
B291505		3.55	0.73	208	2	1.35	20	600	14	0.01	<5	377	0.28	36	20	46
B291506		3.35	0.70	211	2	1.17	20	600	17	0.01	<5	336	0.30	38	20	52
B291507		3.81	0.74	230	1	1.64	20	560	20	0.01	<5	419	0.28	36	10	51
B291508		3.90	0.74	261	4	1.51	21	620	18	0.01	<5	441	0.30	38	90	61
B291509																
B291510		2.32	0.64	411	8	0.13	511	360	157	0.02	10	54	0.24	100	30	663
B291511		3.67	0.53	336	1	0.95	20	550	17	<0.01	<5	358	0.26	33	30	44
B291512		3.62	0.55	275	<1	0.93	20	550	22	<0.01	<5	328	0.26	33	30	36
B291513		3.86	0.57	237	1	1.07	20	570	22	<0.01	7	346	0.26	33	20	34
B291514		3.95	0.48	291	2	1.05	22	570	37	0.01	7	309	0.29	37	20	58
B291515		3.36	0.38	566	7	0.72	20	490	29	0.01	7	264	0.24	32	10	60
B291516		0.03	11.55	145	<1	0.01	3	550	<2	<0.01	<5	108	<0.01	2	<10	8
B291517		3.15	0.40	372	6	0.84	14	1040	23	0.01	<5	244	0.45	71	510	53
B291518		0.40	0.35	238	15	0.09	10	790	9	0.04	<5	44	0.33	67	1700	35
B291519		3.57	1.80	707	11	0.53	38	4130	11	0.01	<5	218	2.18	376	2210	195
B291520		3.59	0.55	262	2	1.11	21	690	21	<0.01	<5	263	0.34	46	80	68
B291521		3.71	0.70	299	1	1.30	20	630	18	<0.01	<5	391	0.32	39	20	37
B291522		3.75	0.71	279	1	1.28	19	640	20	0.01	7	372	0.32	40	30	62
B291523		3.76	0.90	262	1	1.47	19	660	23	0.02	<5	418	0.33	41	30	34
B291524		3.86	0.81	223	1	1.55	20	620	19	0.03	<5	425	0.32	40	30	32
B291525		4.18	0.84	206	1	1.50	20	640	20	0.04	<5	413	0.32	37	40	30
B291526		4.41	0.74	192	3	1.50	20	620	22	0.06	<5	433	0.31	37	40	33
B291527		3.95	0.84	233	2	1.28	18	630	19	0.02	<5	398	0.32	38	40	30
B291528		3.75	0.82	234	1	1.42	17	610	23	0.01	<5	376	0.31	36	30	32
B291529																
B291530		1.73	1.34	414	2	3.19	48	640	20	0.61	<5	208	0.31	90	<10	194
B291531		3.94	0.81	176	2	1.53	17	600	19	0.05	<5	407	0.30	35	40	23
B291532		3.92	0.94	220	2	1.24	19	580	17	0.10	<5	375	0.29	35	30	23
B291533		4.06	0.76	188	4	1.33	16	530	17	0.06	<5	361	0.27	33	30	23
B291534		3.81	0.87	241	2	1.31	18	630	23	0.03	5	402	0.30	36	30	29
B291535		3.74	0.83	306	1	1.31	20	600	28	0.02	7	396	0.31	37	50	62
B291536		0.05	12.15	168	<1	0.02	3	550	2	0.03	<5	112	0.01	3	<10	7
B291537		4.26	0.70	231	<1	1.68	14	500	32	0.02	<5	374	0.25	28	20	45
B291538		3.70	0.88	258	1	1.60	19	630	25	0.03	<5	427	0.31	36	20	49
B291539		3.57	0.89	310	1	1.59	21	650	26	0.06	<5	474	0.32	38	20	59

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291540		1.68	0.127	<0.5	7.57	34	1740	3.0	<2	2.24	<0.5	9	38	29	2.51	0.01
B291541		0.78	0.060	<0.5	6.83	103	1620	2.1	<2	2.64	<0.5	8	42	48	2.28	0.01
B291542		0.88	0.153	<0.5	6.23	86	1500	2.3	5	2.36	<0.5	8	42	70	2.37	0.01
B291543		3.64	1.965	<0.5	7.26	159	1520	2.7	37	2.20	<0.5	7	42	38	2.36	0.01
B291544		3.84	0.177	<0.5	7.43	231	1700	3.0	3	2.15	<0.5	8	38	44	2.37	0.02
B291545		4.62	0.150	<0.5	7.42	267	1880	2.6	<2	2.24	<0.5	7	43	34	2.15	0.02
B291546		5.18	0.082	<0.5	6.82	475	1500	3.1	3	2.48	<0.5	7	42	39	2.33	0.01
B291547		5.56	0.146	<0.5	7.43	506	1690	2.8	<2	2.25	<0.5	6	41	40	2.21	0.02
B291548		2.44	0.042	<0.5	6.35	471	1300	2.9	2	2.45	<0.5	5	29	28	1.92	0.01
B291549		2.46	0.048	<0.5	7.04	430	1400	3.0	<2	2.54	<0.5	6	29	30	2.03	0.01
B291549 A		<0.02	0.053													
B291550		0.10	1.475	<0.5	6.40	1185	700	5.4	<2	0.01	<0.5	4	199	37	3.54	0.05
B291551		5.74	0.110	<0.5	7.09	499	1500	2.8	5	2.29	<0.5	6	68	44	2.16	0.01
B291552		3.04	0.183	<0.5	6.84	972	1460	3.2	5	2.22	<0.5	7	39	30	2.07	0.01
B291553		2.76	0.351	<0.5	7.37	318	1680	3.1	13	1.92	<0.5	6	68	54	2.30	0.02
B291554		4.86	0.035	<0.5	7.10	111	1560	2.9	<2	2.13	<0.5	6	73	26	2.21	0.01
B291555		4.58	0.300	<0.5	7.01	186	1660	3.0	8	2.58	<0.5	8	39	25	2.46	0.01
B291556		1.48	<0.005	<0.5	0.14	<5	20	<0.5	<2	19.60	<0.5	<1	8	1	0.12	<0.01
B291557		4.54	0.085	<0.5	7.44	234	1600	3.2	4	2.22	<0.5	8	39	28	2.28	0.01
B291558		3.24	0.049	<0.5	7.15	235	1590	3.0	3	2.72	<0.5	7	69	30	2.44	0.01
B291559		3.40	0.339	<0.5	6.49	1140	1180	2.9	17	3.86	0.8	9	38	28	2.25	0.02
B291560		3.86	0.055	<0.5	6.44	326	1510	2.7	<2	2.77	<0.5	8	72	28	2.07	0.01
B291561		3.04	0.121	<0.5	6.47	327	1260	2.7	2	2.39	<0.5	7	34	28	2.15	0.01
B291562		2.38	0.044	<0.5	6.89	392	1300	2.8	<2	2.17	<0.5	8	62	26	2.09	0.01
B291563		5.20	0.092	<0.5	6.48	521	1170	2.7	5	1.90	<0.5	7	35	22	2.15	0.02
B291564		3.68	0.039	<0.5	7.05	70	1430	2.8	<2	2.02	<0.5	7	66	21	2.37	0.01
B291565		5.48	0.099	<0.5	6.50	83	1310	2.6	2	2.23	<0.5	6	35	24	2.14	0.01
B291566		3.40	0.084	<0.5	6.27	166	1370	2.2	3	1.84	<0.5	7	77	27	1.80	0.01
B291567		3.94	0.308	<0.5	6.68	158	1480	2.5	4	2.58	<0.5	7	37	30	2.19	0.01
B291568		5.26	0.017	<0.5	7.70	56	1460	3.1	2	1.90	<0.5	7	74	17	2.14	0.01
B291569		<0.02	0.018													
B291570		0.10	0.091	0.5	7.10	114	590	2.7	<2	0.53	<0.5	61	1245	414	8.40	0.03
B291571		3.14	0.061	<0.5	6.43	36	1420	2.6	3	2.49	<0.5	10	39	57	2.31	0.01
B291572		4.48	0.077	<0.5	6.98	58	1460	2.7	<2	2.13	<0.5	8	78	36	2.27	0.01
B291573		4.80	0.020	<0.5	7.86	38	1570	2.9	<2	2.41	0.5	8	43	32	2.53	0.02
B291574		3.88	0.077	<0.5	6.51	312	1250	2.3	6	2.29	<0.5	8	45	63	2.14	<0.01
B291575		2.56	0.640	<0.5	7.66	90	1530	2.9	43	2.14	<0.5	9	41	46	2.38	<0.01
B291576		1.56	<0.005	<0.5	0.13	<5	10	<0.5	<2	19.70	<0.5	<1	1	1	0.13	<0.01
B291577		5.74	0.032	<0.5	7.22	76	1590	2.9	<2	2.35	<0.5	8	45	40	2.43	0.01
B291578		5.94	0.095	<0.5	7.88	95	1670	3.1	7	2.23	<0.5	9	47	39	2.51	0.01

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291540		3.40	0.87	266	2	1.68	20	650	25	0.11	<5	453	0.33	38	30	53
B291541		3.86	0.77	244	25	1.10	21	550	17	0.27	<5	402	0.26	31	120	31
B291542		3.51	0.78	247	21	1.19	20	540	20	0.31	<5	391	0.27	31	30	33
B291543		3.46	0.78	255	5	1.30	20	600	37	0.28	6	385	0.30	36	20	70
B291544		3.59	0.86	194	2	1.57	18	630	20	0.08	5	427	0.31	37	30	23
B291545		4.60	0.76	173	7	1.39	18	610	19	0.11	<5	414	0.30	38	30	21
B291546		3.63	0.83	265	3	1.03	20	580	20	0.01	6	369	0.30	37	30	36
B291547		4.07	0.80	179	2	1.40	17	600	21	0.01	5	392	0.29	35	30	21
B291548		3.57	0.67	214	1	0.95	16	490	22	0.01	5	321	0.25	29	20	28
B291549		3.81	0.72	216	2	1.16	15	510	22	0.01	6	365	0.26	30	30	27
B291549 A																
B291550		2.58	0.33	82	2	0.10	18	290	25	0.01	106	86	0.19	85	10	40
B291551		3.63	0.77	235	2	1.25	19	580	26	0.03	<5	395	0.29	33	40	41
B291552		3.80	0.72	233	3	1.40	17	540	27	0.04	<5	388	0.27	32	30	44
B291553		4.01	0.73	231	1	1.55	17	580	22	0.02	<5	405	0.29	34	30	38
B291554		3.75	0.72	273	1	1.61	20	580	28	0.05	<5	417	0.29	33	20	56
B291555		3.48	0.72	301	1	1.52	22	620	27	0.08	5	456	0.32	38	20	56
B291556		0.03	11.70	152	<1	0.02	5	510	<2	0.01	<5	110	<0.01	3	<10	7
B291557		3.80	0.75	274	<1	1.62	21	580	27	0.07	<5	430	0.30	36	20	55
B291558		3.59	0.55	306	<1	1.65	24	670	18	0.11	11	471	0.32	40	20	56
B291559		3.38	0.51	382	3	1.04	23	560	93	0.15	17	396	0.28	34	20	193
B291560		3.47	0.50	290	3	1.31	23	550	25	0.05	10	459	0.28	34	20	54
B291561		3.22	0.60	271	3	1.11	20	530	26	0.04	<5	429	0.28	33	30	64
B291562		3.27	0.61	248	1	1.09	22	550	26	0.04	<5	392	0.28	33	30	65
B291563		3.49	0.70	240	5	1.12	20	520	24	0.04	<5	377	0.26	31	30	57
B291564		3.45	0.68	297	1	1.39	22	600	19	0.10	8	440	0.29	35	10	60
B291565		3.32	0.79	276	2	1.35	17	520	22	0.07	5	393	0.24	29	20	49
B291566		3.38	0.51	211	7	1.24	18	510	16	0.05	<5	372	0.24	30	20	42
B291567		3.50	0.61	285	3	1.03	23	550	20	0.02	6	358	0.28	34	30	53
B291568		3.90	0.52	247	1	1.60	18	530	30	0.02	6	400	0.27	32	10	55
B291569																
B291570		2.31	0.59	385	9	0.13	502	360	141	0.02	12	53	0.20	94	20	611
B291571		3.54	0.61	260	3	1.31	23	570	17	0.20	10	452	0.27	33	10	46
B291572		3.55	0.62	269	3	1.41	22	560	20	0.19	11	399	0.27	34	10	54
B291573		3.79	0.76	352	2	1.38	21	650	34	0.17	7	428	0.32	38	20	170
B291574		3.59	0.58	230	3	1.18	19	520	18	0.30	7	369	0.25	30	100	35
B291575		4.08	0.67	228	2	1.49	23	620	21	0.22	7	376	0.31	38	70	49
B291576		0.03	11.15	168	<1	0.02	3	480	3	<0.01	<5	112	<0.01	2	10	7
B291577		3.63	0.76	270	3	1.66	23	580	19	0.20	<5	486	0.30	37	20	52
B291578		4.17	0.85	254	3	1.75	26	650	24	0.19	5	475	0.33	39	30	51

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291579		4.18	0.018	<0.5	7.41	67	1420	2.8	3	2.59	<0.5	8	44	23	2.25	0.01
B291580		5.44	0.164	<0.5	7.66	23	1710	3.0	12	2.57	<0.5	9	49	28	2.54	<0.01
B291581		2.86	0.341	<0.5	7.78	114	1620	2.7	9	2.31	<0.5	8	48	52	2.55	<0.01
B291582		3.22	0.087	<0.5	7.51	158	1670	2.8	3	2.42	<0.5	8	52	37	2.51	<0.01
B291583		2.62	0.319	<0.5	7.83	132	1720	2.6	10	2.17	<0.5	8	46	47	2.37	<0.01
B291584		1.16	0.029	<0.5	8.54	54	1970	2.1	6	1.63	<0.5	7	47	64	2.24	<0.01
B291585		6.16	0.024	<0.5	7.36	74	1530	2.9	2	2.34	<0.5	7	48	26	2.32	<0.01
B291586		3.84	0.032	<0.5	7.98	55	1610	3.1	<2	2.65	<0.5	7	46	28	2.47	<0.01
B291587		3.66	0.050	<0.5	8.05	189	1590	3.3	5	2.46	<0.5	7	42	27	2.43	<0.01
B291588		2.08	0.239	<0.5	7.15	281	1420	2.8	7	1.95	<0.5	6	44	39	2.09	<0.01
B291589		<0.02	0.136													
B291590		0.10	3.26	1.3	6.97	12	2100	3.2	<2	4.71	<0.5	23	141	102	4.95	0.01
B291591		3.30	0.153	0.7	7.49	269	1040	2.8	6	3.01	0.5	9	42	47	2.47	0.01
B291592		7.20	0.020	<0.5	7.66	29	1600	3.0	2	2.37	<0.5	8	47	25	2.42	0.01
B291593		6.40	0.349	<0.5	8.01	1060	1740	2.9	12	2.52	<0.5	7	45	21	2.49	0.01
B291594		5.64	0.045	<0.5	7.78	63	1660	3.0	7	2.44	<0.5	7	45	22	2.44	0.01
B291595		6.66	0.210	<0.5	8.14	136	1660	3.1	3	2.52	<0.5	8	44	23	2.54	0.01
B291596		1.68	<0.005	<0.5	0.13	<5	20	<0.5	<2	19.05	<0.5	<1	3	1	0.12	<0.01
B291597		6.70	0.027	<0.5	7.39	126	1500	3.1	<2	2.30	<0.5	7	43	24	2.28	<0.01
B291598		4.70	0.012	<0.5	7.43	6	1600	3.0	<2	2.58	<0.5	8	44	18	2.44	0.01
B291599		5.52	0.023	<0.5	7.21	68	1340	2.9	<2	2.55	<0.5	6	43	8	2.25	0.01
B291600		6.34	0.014	<0.5	6.92	48	1500	2.9	<2	2.50	<0.5	8	44	18	2.36	0.01
B291601		2.84	0.009	<0.5	6.87	96	1480	3.0	<2	2.53	<0.5	8	42	13	2.30	0.01
B291602		3.10	1.910	<0.5	7.68	138	1470	3.1	112	2.54	<0.5	7	43	44	2.32	0.01
B291603		6.22	0.041	<0.5	6.79	292	1410	3.0	6	2.55	<0.5	7	44	31	2.19	0.01
B291604		6.18	0.018	<0.5	7.76	85	1610	3.1	<2	2.58	<0.5	7	45	24	2.43	<0.01
B291605		5.88	0.285	<0.5	7.73	881	1620	3.1	12	2.65	<0.5	23	42	27	2.46	<0.01
B291606		6.50	0.165	<0.5	7.38	183	1730	3.0	6	2.89	<0.5	8	46	34	2.59	<0.01
B291607		5.96	0.068	<0.5	7.98	127	1700	3.1	5	2.63	<0.5	10	51	39	2.52	<0.01
B291608		4.72	0.015	<0.5	7.63	51	1380	3.2	2	2.40	<0.5	6	44	13	2.09	<0.01
B291609		<0.02	0.012													

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 23-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05044876

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291579		3.65	0.74	277	5	1.65	21	600	22	0.11	<5	455	0.30	36	20	57
B291580		3.98	0.83	305	3	1.78	22	670	28	0.15	<5	538	0.33	40	90	67
B291581		3.99	0.84	246	4	1.58	28	640	22	0.26	<5	506	0.32	38	100	52
B291582		3.81	0.82	284	4	1.74	24	660	24	0.19	<5	525	0.33	40	50	64
B291583		4.88	0.79	252	5	1.56	24	650	20	0.24	<5	505	0.32	37	760	54
B291584		4.13	0.73	170	3	1.31	22	750	17	0.36	<5	490	0.30	37	60	33
B291585		3.58	0.79	282	2	1.71	22	610	26	0.11	<5	492	0.31	37	50	64
B291586		3.66	0.81	272	1	1.87	26	640	23	0.19	<5	528	0.32	38	20	48
B291587		3.97	0.79	287	5	1.81	23	610	27	0.21	<5	503	0.30	35	50	55
B291588		4.23	0.65	197	8	1.48	17	540	19	0.25	<5	407	0.26	32	50	38
B291589																
B291590		3.52	2.90	1045	13	2.33	68	2280	26	0.31	<5	1670	0.38	164	<10	92
B291591		3.61	0.72	604	2	1.06	21	620	54	0.29	25	280	0.29	36	100	120
B291592		3.76	0.82	314	1	1.80	22	620	24	0.10	6	505	0.32	38	10	71
B291593		4.23	0.84	292	17	1.82	27	690	24	0.19	<5	538	0.32	38	50	55
B291594		3.52	0.85	286	3	1.77	23	640	22	0.15	<5	509	0.32	38	20	53
B291595		3.67	0.87	301	1	1.84	25	660	19	0.18	<5	531	0.32	37	<10	48
B291596		0.03	11.05	146	<1	0.02	4	490	<2	0.01	<5	114	0.01	1	10	9
B291597		3.80	0.76	267	1	1.69	23	580	22	0.16	<5	482	0.30	36	60	47
B291598		3.34	0.84	308	2	1.78	24	620	22	0.11	<5	522	0.33	40	<10	58
B291599		3.20	0.55	299	1	1.05	20	560	21	0.02	<5	411	0.29	36	20	57
B291600		3.44	0.70	303	1	1.50	21	570	21	0.12	<5	457	0.30	36	10	55
B291601		3.56	0.69	286	1	1.68	23	580	20	0.10	<5	468	0.29	36	10	47
B291602		3.81	0.74	264	2	1.60	18	590	25	0.14	<5	497	0.29	35	10	44
B291603		3.64	0.66	255	5	1.56	23	550	18	0.18	<5	464	0.28	34	20	44
B291604		3.63	0.79	297	4	1.81	23	630	22	0.16	<5	533	0.32	39	20	59
B291605		3.79	0.77	281	2	1.84	21	620	24	0.23	<5	542	0.31	38	<10	51
B291606		3.58	0.94	293	2	1.81	24	650	18	0.22	<5	572	0.33	41	10	49
B291607		3.82	0.83	280	2	1.80	26	640	20	0.22	<5	550	0.33	39	30	55
B291608		3.73	0.67	274	<1	1.77	20	540	30	0.07	<5	476	0.27	36	<10	63
B291609																

Comments: Additional Au values for samples B291578, B291580 and B291581 are 0.275, 1.995 and 0.115ppm respectively.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Dat J-JUN-2005
Account: STRGOL

CERTIFICATE VA05046431

Project: Dublin Gulch-1735

P.O. No.:

This report is for 22 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 13-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046431

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291610		0.10	1.350	<0.5	6.81	1275	730	5.6	3	0.01	<0.5	4	211	39	3.71	0.06
B291611		5.80	0.047	<0.5	7.32	226	1270	3.1	2	1.94	<0.5	6	27	21	2.06	0.01
B291612		6.06	0.040	<0.5	7.26	244	1520	2.8	2	2.26	<0.5	7	70	23	2.27	<0.01
B291613		4.36	0.046	<0.5	7.38	39	1520	2.4	8	2.03	<0.5	8	26	29	2.32	<0.01
B291614		1.30	0.010	<0.5	7.20	36	1640	2.8	<2	2.05	<0.5	8	28	21	2.35	<0.01
B291615		6.22	0.310	<0.5	7.22	72	1460	2.7	51	1.98	<0.5	7	72	53	2.36	<0.01
B291616		1.50	<0.005	<0.5	0.11	<5	20	<0.5	<2	18.85	<0.5	<1	4	2	0.10	<0.01
B291617		6.32	0.159	<0.5	7.25	44	1230	2.9	12	2.22	0.7	7	28	38	2.31	0.02
B291618		4.06	0.077	<0.5	7.35	231	850	2.9	<2	2.04	2.2	7	66	41	2.67	0.06
B291619		4.80	0.060	<0.5	6.80	130	1380	2.9	4	2.00	<0.5	8	27	33	2.17	0.01
B291620		1.36	0.460	<0.5	5.27	91	810	1.9	35	3.02	<0.5	6	87	30	1.88	0.01
B291621		2.16	0.015	<0.5	7.14	53	1560	3.0	<2	2.25	<0.5	7	27	25	2.30	0.01
B291622		2.18	0.011	<0.5	6.91	20	1500	2.9	<2	2.15	<0.5	7	61	16	2.16	0.01
B291623		10.78	0.049	<0.5	6.53	257	1360	3.2	<2	2.04	<0.5	11	33	41	2.09	0.01
B291624		5.60	0.025	<0.5	7.05	160	1140	3.3	<2	2.87	<0.5	6	46	25	2.02	<0.01
B291625		4.48	0.019	<0.5	6.94	172	1570	2.3	2	2.30	<0.5	8	25	22	2.17	<0.01
B291626		6.58	0.043	<0.5	6.63	102	1580	3.0	2	2.50	<0.5	7	63	28	2.23	<0.01
B291627		5.74	0.062	<0.5	7.28	246	1360	3.1	4	2.19	<0.5	8	25	28	2.34	<0.01
B291628		6.18	0.031	<0.5	7.10	94	1500	2.6	<2	2.62	<0.5	7	60	47	2.22	<0.01
B291629		0.04	0.030													
B291630		0.10	4.34	8.6	7.63	7	480	0.9	<2	2.66	1.3	18	22	122	3.95	<0.01
B291631		5.36	0.024	<0.5	7.45	60	1530	2.8	<2	2.27	<0.5	8	59	25	2.38	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 20-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046431

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291610		2.70	0.34	90	2	0.10	20	310	30	0.02	115	85	0.23	90	10	43
B291611		3.59	0.60	259	2	1.57	16	470	34	0.11	<5	369	0.24	29	30	60
B291612		3.54	0.72	289	1	1.62	19	590	28	0.12	<5	439	0.30	36	10	73
B291613		3.72	0.73	294	1	1.37	19	560	27	0.08	10	368	0.28	35	30	64
B291614		3.28	0.73	295	1	1.41	18	610	23	0.10	6	392	0.29	37	20	65
B291615		3.76	0.63	229	4	1.38	22	550	21	0.34	6	374	0.26	33	100	49
B291616		0.03	11.30	157	<1	0.01	4	520	<2	0.01	<5	102	<0.01	3	<10	7
B291617		3.72	0.62	286	14	1.33	16	530	53	0.44	13	328	0.26	32	50	237
B291618		3.46	0.74	326	<1	0.48	19	560	69	1.42	20	184	0.26	33	20	519
B291619		3.58	0.62	269	4	1.51	19	520	32	0.22	8	367	0.26	32	20	81
B291620		2.40	0.46	323	<1	0.68	11	380	34	0.37	12	279	0.18	22	10	43
B291621		3.54	0.71	317	1	1.58	18	570	31	0.11	5	412	0.29	35	10	69
B291622		3.50	0.66	302	1	1.56	16	560	32	0.11	5	400	0.27	33	20	68
B291623		3.99	0.64	257	1	1.44	24	520	27	0.18	<5	358	0.34	41	10	68
B291624		3.16	0.74	260	2	0.87	17	520	24	0.12	10	302	0.26	32	20	46
B291625		3.35	0.75	282	1	1.17	20	570	19	0.15	<5	328	0.28	34	20	51
B291626		3.41	0.77	271	2	1.19	19	590	22	0.13	<5	352	0.30	37	20	53
B291627		3.44	0.82	286	1	1.00	18	560	34	0.09	13	322	0.28	34	20	68
B291628		3.53	0.78	314	1	1.25	21	560	24	0.07	13	401	0.29	36	20	57
B291629																
B291630		2.24	1.28	930	11	1.55	13	840	19	0.65	<5	368	0.37	146	<10	95
B291631		3.49	0.79	307	1	1.53	20	600	28	0.15	<5	414	0.31	37	20	62

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Dat -OCT-2005
Account: STRGOL

CERTIFICATE VA05046971

Project: Dublin Gulch-1735

P.O. No.:

This report is for 193 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Au-GRA21	Au 30g FA-GRAV finish	WST-SIM

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B291632		4.16	0.297				<0.5	7.31	358	1680	2.9	21	1.80	<0.5	7	111
B291633		5.10	0.175				<0.5	7.77	248	1520	2.9	13	1.81	<0.5	7	127
B291634		1.52	0.227				<0.5	7.11	281	1590	2.9	11	1.64	<0.5	7	78
B291635		2.98	0.083				<0.5	7.81	288	1680	3.0	13	1.80	<0.5	8	133
B291636		2.00	<0.005				<0.5	0.10	7	20	<0.5	<2	19.20	<0.5	<1	7
B291637		2.78	0.471				<0.5	7.31	272	1460	2.8	12	1.69	<0.5	7	123
B291638		4.94	5.25				<0.5	7.49	527	1600	2.8	109	1.76	<0.5	9	82
B291639		4.04	0.364				<0.5	7.04	677	1440	2.5	21	1.86	<0.5	9	130
B291640		3.30	0.280				<0.5	6.98	526	1560	2.7	23	1.48	<0.5	8	91
B291641		1.60	0.780				<0.5	7.22	505	1490	2.7	33	1.56	<0.5	10	116
B291642		1.76	0.432				<0.5	7.17	375	1650	2.9	7	1.78	<0.5	10	80
B291643		1.32	0.149				<0.5	7.49	276	1630	3.0	14	2.16	<0.5	9	118
B291644		3.66	1.290				<0.5	7.54	1345	1480	2.8	62	1.32	<0.5	11	102
B291645		3.02	0.969				<0.5	7.23	1325	1560	2.4	23	1.12	<0.5	10	121
B291646		1.90	0.440				<0.5	7.85	1085	1760	2.8	18	1.29	<0.5	8	81
B291647		1.04	0.301				0.5	7.27	1250	1320	2.7	10	1.73	0.7	8	132
B291648		6.04	1.030				<0.5	7.67	1025	1460	2.8	53	2.66	<0.5	14	95
B291649			1.215													
B291650		0.10	0.416				2.8	9.79	6	1140	1.3	<2	1.62	<0.5	9	9
B291651		1.04	2.51				0.7	7.07	741	1560	2.5	34	1.80	<0.5	8	139
B291652		2.64	0.880				0.5	7.53	968	1530	2.8	26	1.36	<0.5	13	92
B291653		1.54	1.045				<0.5	8.03	756	1610	3.0	52	1.49	<0.5	11	159
B291654		2.02	0.124				<0.5	7.67	441	1600	3.0	<2	1.98	<0.5	10	82
B291655		2.92	0.748				<0.5	7.57	315	1550	2.8	24	1.72	<0.5	9	129
B291656		1.76	<0.005				<0.5	0.11	<5	20	<0.5	<2	21.4	<0.5	1	9
B291657		2.76	0.109				<0.5	7.12	432	1500	2.8	<2	2.45	<0.5	10	129
B291658		1.22	0.325				<0.5	7.26	853	1600	2.7	3	1.20	0.6	11	79
B291659		6.72	2.21				<0.5	7.48	551	1520	2.9	54	1.71	<0.5	13	122
B291660		5.52	0.383				<0.5	7.55	434	1500	2.9	24	1.85	<0.5	11	83
B291661		3.96	0.359				<0.5	7.46	336	1580	2.9	12	2.36	<0.5	11	121
B291662		3.54	0.263				<0.5	7.45	268	1560	2.9	9	2.08	<0.5	10	90
B291663		6.60	0.618				<0.5	7.21	350	1440	2.9	16	2.20	<0.5	12	121
B291664		5.34	0.768				<0.5	7.30	513	1520	2.9	3	2.22	<0.5	11	96
B291665		6.74	0.499				<0.5	7.38	1050	1400	2.8	50	1.70	<0.5	13	131
B291666		6.86	0.367				<0.5	7.42	908	1460	2.8	7	2.14	<0.5	11	94
B291667		4.92	0.470				<0.5	6.67	663	1460	2.7	10	2.18	<0.5	9	116
B291668		6.24	0.356				1.0	7.43	888	1180	2.8	7	2.92	1.1	9	83
B291669			0.406													
B291670		0.10	0.754				2.3	7.68	8	460	0.7	<2	1.89	1.3	24	106
B291671		5.50	0.135				<0.5	7.88	580	1600	2.8	3	2.20	<0.5	11	127

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B291632		54	2.31	0.02	3.95	0.76	163	1	1.58	23	590	18	0.13	<5	436	0.28
B291633		47	2.20	0.02	3.80	0.76	144	1	1.61	21	600	18	0.03	<5	432	0.28
B291634		46	2.25	0.01	3.77	0.76	166	1	1.55	19	610	18	0.01	5	398	0.29
B291635		44	2.40	0.02	3.92	0.79	178	1	1.53	21	640	16	0.02	7	403	0.31
B291636		1	0.09	<0.01	0.03	11.40	144	<1	0.01	5	490	2	0.01	<5	106	<0.01
B291637		40	2.16	0.02	3.56	0.67	176	1	1.43	20	550	22	0.03	6	368	0.26
B291638		59	2.39	<0.01	3.94	0.77	183	1	1.46	22	630	20	0.05	8	391	0.29
B291639		88	2.27	<0.01	3.52	0.59	184	4	1.40	21	570	17	0.03	10	354	0.26
B291640		50	2.14	0.01	3.77	0.67	154	1	1.44	20	600	16	0.02	5	375	0.28
B291641		49	2.19	0.01	3.82	0.70	174	1	1.47	20	580	18	0.02	6	391	0.28
B291642		52	2.37	0.01	3.68	0.75	182	1	1.57	23	630	18	0.02	<5	426	0.30
B291643		43	2.65	0.03	3.71	0.89	238	1	1.67	23	660	17	0.04	5	467	0.32
B291644		109	2.83	0.08	3.65	0.69	200	3	1.31	19	650	19	0.04	17	354	0.29
B291645		69	2.21	0.02	4.01	0.30	178	2	1.11	19	580	29	0.06	28	217	0.26
B291646		52	2.35	0.03	4.10	0.44	205	3	1.32	19	650	36	0.05	24	306	0.30
B291647		66	2.59	0.04	3.68	0.31	263	5	0.84	17	610	62	0.03	35	152	0.26
B291648		80	2.95	0.02	3.86	0.47	429	5	0.87	18	670	35	0.02	23	241	0.30
B291649																
B291650		7810	3.51	0.03	3.90	1.26	512	3	3.62	13	2050	10	0.26	<5	732	0.36
B291651		35	2.03	0.01	4.11	0.36	232	3	0.97	17	590	46	0.03	25	256	0.26
B291652		70	2.54	0.01	4.06	0.56	190	2	1.20	20	600	48	0.03	27	312	0.27
B291653		57	2.10	0.01	4.55	0.60	198	1	1.43	19	590	32	0.02	9	372	0.28
B291654		38	2.20	0.01	3.92	0.77	209	1	1.62	19	640	20	0.02	<5	456	0.31
B291655		36	2.17	0.01	3.79	0.78	234	1	1.44	20	600	24	0.02	<5	411	0.29
B291656		2	0.10	<0.01	0.03	12.25	151	<1	0.01	4	540	<2	0.01	<5	123	<0.01
B291657		26	2.54	0.01	3.38	0.66	289	2	1.55	21	650	26	0.03	8	386	0.32
B291658		52	2.26	0.02	3.89	0.53	203	2	1.12	16	580	32	0.04	17	283	0.27
B291659		61	2.43	0.01	3.77	0.80	222	1	1.27	20	610	37	0.03	8	360	0.29
B291660		53	2.31	0.03	3.84	0.78	225	<1	1.41	23	590	18	0.03	5	404	0.28
B291661		43	2.54	0.02	4.00	0.95	302	1	1.54	17	640	20	0.01	5	464	0.30
B291662		35	2.46	0.01	3.90	0.94	277	1	1.49	16	620	18	0.01	<5	435	0.29
B291663		55	2.58	0.01	3.82	0.98	302	1	1.54	16	610	20	0.02	<5	445	0.29
B291664		58	2.65	0.01	3.68	0.98	294	1	1.58	17	650	17	0.03	<5	483	0.30
B291665		91	2.53	0.01	4.01	0.89	236	8	1.45	15	580	20	0.07	<5	409	0.27
B291666		46	2.40	0.01	3.71	0.93	282	2	1.27	19	590	24	0.03	<5	386	0.27
B291667		37	2.21	0.01	3.86	0.79	267	<1	1.05	16	540	34	0.02	10	330	0.25
B291668		48	2.20	0.03	3.43	0.58	386	4	1.04	16	570	324	0.09	87	320	0.28
B291669																
B291670		2120	5.08	0.01	1.77	1.33	427	2	3.15	48	670	22	0.64	<5	212	0.31
B291671		51	2.38	0.01	3.77	0.82	233	1	1.48	23	600	25	0.07	5	434	0.30

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291632		34	40	31
B291633		34	40	38
B291634		35	30	60
B291635		38	20	68
B291636		2	<10	7
B291637		32	60	64
B291638		37	50	61
B291639		33	70	48
B291640		35	60	47
B291641		35	60	40
B291642		37	50	43
B291643		44	20	46
B291644		48	40	54
B291645		34	80	37
B291646		39	60	47
B291647		38	210	116
B291648		48	30	72
B291649				
B291650		182	<10	62
B291651		34	30	57
B291652		34	30	95
B291653		38	50	53
B291654		37	40	47
B291655		35	30	44
B291656		1	<10	7
B291657		40	10	54
B291658		34	10	71
B291659		36	30	53
B291660		36	30	46
B291661		43	30	49
B291662		42	30	45
B291663		45	30	49
B291664		48	50	47
B291665		41	1140	35
B291666		42	30	45
B291667		33	20	85
B291668		35	30	145
B291669				
B291670		91	<10	203
B291671		37	30	49

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B291672		5.82	0.156				<0.5	8.10	579	1740	3.0	2	2.10	<0.5	13	84
B291673		5.42	0.191				<0.5	7.74	900	1620	3.0	8	1.94	<0.5	11	123
B291674		6.22	2.30				<0.5	7.39	724	1680	2.9	19	1.66	0.5	13	86
B291675		5.64	1.055				<0.5	7.34	1070	1600	2.9	9	1.84	<0.5	13	123
B291676		1.48	<0.005				<0.5	0.12	7	20	<0.5	<2	19.40	<0.5	2	9
B291677		6.08	2.28				<0.5	6.98	620	1560	2.7	30	1.80	<0.5	11	123
B291678		5.80	0.279				<0.5	7.05	328	1080	2.7	9	1.42	<0.5	8	77
B291679		5.00	0.071				<0.5	7.40	383	1240	3.3	<2	1.71	<0.5	8	118
B291680		3.24	0.103				<0.5	7.38	866	1660	2.9	2	2.45	<0.5	10	91
B291681		3.86	0.261				0.9	7.70	1275	1360	3.1	3	1.38	1.2	9	115
B291682		3.52	0.071				<0.5	7.61	772	1440	3.1	<2	1.56	1.0	7	85
B291683		4.66	0.250				0.7	7.59	1000	1530	2.7	4	0.54	1.4	11	121
B291684		6.80	0.177				<0.5	7.83	561	1630	2.8	<2	1.40	0.8	8	83
B291685		6.96	0.138				<0.5	7.43	1750	1740	2.8	<2	2.14	<0.5	16	110
B291686		3.18	0.804				<0.5	7.39	548	1580	3.0	2	2.27	<0.5	9	84
B291687		2.04	0.168				1.2	7.07	1755	1370	3.3	10	1.66	1.2	10	120
B291688		4.94	0.323				0.5	7.48	636	1540	2.5	9	1.61	0.8	7	72
B291689			0.315													
B291690		0.10	0.417				2.5	8.82	<5	1040	1.2	<2	1.49	<0.5	7	9
B291691		6.20	0.530				1.3	7.14	867	1460	2.5	13	2.23	0.9	12	108
B291692		4.88	0.424				1.1	6.79	518	1360	2.6	10	2.42	0.8	7	82
B291693		5.84	0.378				0.5	7.81	450	1590	2.8	10	2.04	0.5	10	129
B291694		5.52	1.235				0.9	7.82	2660	1630	2.7	29	2.11	0.6	35	73
B291695		4.86	0.506				1.1	7.54	383	1240	2.8	28	1.81	0.7	9	106
B291696		1.40	<0.005				<0.5	0.15	7	20	<0.5	<2	20.3	<0.5	<1	6
B291697		6.12	0.510				0.6	7.22	1995	1130	2.4	12	2.23	<0.5	11	121
B291698		5.16	0.198				<0.5	7.82	182	1650	2.7	<2	2.04	<0.5	7	71
B291699		6.28	0.278				<0.5	7.47	206	1540	2.8	7	2.00	<0.5	9	115
B291700		4.74	0.510				<0.5	7.48	745	1520	2.5	11	1.97	<0.5	16	77
B291701		1.12	0.447				<0.5	5.17	218	900	1.9	28	2.47	<0.5	8	150
B291702		1.10	0.915				<0.5	5.54	261	950	2.0	19	2.43	<0.5	7	98
B291703		2.72	0.110				<0.5	7.36	368	900	2.8	<2	2.53	2.1	7	127
B291704		2.58	0.117				0.7	7.95	131	790	2.9	<2	2.25	2.2	6	74
B291705		4.36	0.098				0.6	7.74	376	1240	2.9	2	1.86	1.1	8	103
B291706		2.58	2.97				4.1	7.79	1125	670	4.1	79	1.46	3.1	10	71
B291707		2.48	2.75				6.1	7.14	5100	570	2.6	91	1.65	7.8	30	128
B291708		2.32	1.390				8.5	7.52	4260	430	2.4	17	0.54	0.9	13	93
B291709			1.495													
B291710		0.10	4.43				9.2	8.27	23	490	0.9	<2	2.83	1.6	18	21
B291711		4.64	0.564				11.1	7.48	2810	560	2.9	13	1.06	2.3	15	154

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B291672		47	2.43	0.01	3.60	0.86	236	<1	1.67	21	660	23	0.06	<5	481	0.31
B291673		50	2.32	0.01	3.93	0.83	215	2	1.50	19	610	23	0.09	<5	438	0.30
B291674		70	2.38	<0.01	3.81	0.81	191	2	1.42	19	620	19	0.04	8	409	0.29
B291675		65	2.28	<0.01	4.10	0.76	333	3	1.51	23	610	21	0.12	7	433	0.29
B291676		2	0.11	<0.01	0.03	11.45	151	<1	0.01	1	450	<2	0.02	<5	110	<0.01
B291677		57	2.19	0.04	3.92	0.73	186	1	1.46	19	570	22	0.09	10	413	0.29
B291678		37	1.48	0.03	4.70	0.46	165	1	1.25	13	370	32	0.02	8	296	0.18
B291679		31	1.96	0.03	4.17	0.62	240	1	1.52	16	490	31	0.03	6	354	0.25
B291680		51	2.38	0.03	3.62	0.75	294	1	1.38	22	610	24	0.03	12	429	0.30
B291681		72	2.58	0.04	3.87	0.55	343	2	1.01	21	610	109	0.15	44	262	0.26
B291682		50	2.36	0.03	3.95	0.57	364	2	1.08	21	610	75	0.10	32	277	0.26
B291683		106	3.00	0.03	4.33	0.37	285	3	0.85	18	570	86	0.12	29	192	0.22
B291684		50	2.54	0.02	4.04	0.56	305	5	1.22	17	630	41	0.10	19	293	0.26
B291685		47	2.59	0.01	4.02	0.69	313	2	1.31	19	650	54	0.34	25	389	0.29
B291686		34	2.42	0.02	3.68	0.66	380	3	1.13	19	660	57	0.14	27	355	0.29
B291687		64	2.45	0.02	3.79	0.58	404	4	0.44	17	650	134	0.16	42	197	0.27
B291688		56	2.45	0.02	4.01	0.60	446	3	0.76	18	590	99	0.31	29	233	0.23
B291689																
B291690		7200	3.13	0.02	3.64	1.11	471	3	3.39	10	1880	10	0.23	<5	681	0.33
B291691		69	2.36	0.02	3.74	0.66	502	7	0.79	19	620	86	0.21	42	280	0.28
B291692		40	2.40	0.03	3.93	0.64	655	2	0.81	18	580	132	0.19	45	297	0.28
B291693		55	2.30	0.02	3.97	0.62	322	3	1.19	23	590	65	0.18	29	370	0.28
B291694		55	2.46	0.02	3.95	0.66	328	2	1.05	25	640	80	0.36	43	346	0.30
B291695		53	2.27	0.03	3.76	0.62	474	2	0.76	23	630	83	0.15	56	263	0.28
B291696		2	0.11	<0.01	0.04	11.70	163	<1	0.02	5	500	<2	<0.01	<5	120	<0.01
B291697		53	2.63	0.11	3.45	0.60	333	2	1.24	21	600	87	0.13	66	368	0.28
B291698		29	2.26	0.07	3.93	0.60	259	3	1.38	23	630	24	0.08	29	379	0.29
B291699		23	2.19	0.05	3.77	0.42	270	3	1.38	20	580	29	0.05	29	404	0.27
B291700		80	2.59	0.04	3.89	0.55	287	4	1.32	26	610	21	0.20	31	376	0.28
B291701		43	2.00	0.03	2.63	0.72	333	8	0.74	21	410	11	0.07	16	308	0.18
B291702		41	2.01	0.02	2.83	0.72	320	7	0.85	17	450	16	0.04	16	322	0.19
B291703		45	2.63	0.07	3.37	0.85	596	2	0.78	17	580	61	0.20	34	314	0.25
B291704		29	2.79	0.07	3.61	0.74	923	2	0.14	20	590	114	0.10	38	155	0.27
B291705		35	2.37	0.04	3.90	0.58	552	2	0.56	22	550	67	0.23	18	209	0.26
B291706		70	2.04	0.05	3.04	0.45	466	2	0.12	20	660	188	0.69	105	120	0.25
B291707		75	3.19	0.08	3.13	0.42	553	4	0.05	20	460	497	1.36	274	146	0.23
B291708		39	4.52	0.08	3.22	0.29	86	5	0.05	27	370	1460	1.07	663	161	0.26
B291709																
B291710		121	4.19	0.02	2.27	1.34	962	13	1.67	15	920	25	0.69	<5	421	0.38
B291711		69	2.57	0.05	3.24	0.37	757	3	0.50	25	530	106	0.50	70	138	0.25

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291672		38	20	54
B291673		37	40	63
B291674		36	50	73
B291675		36	60	65
B291676		1	<10	7
B291677		36	20	52
B291678		21	30	41
B291679		30	50	67
B291680		36	30	63
B291681		35	20	178
B291682		33	20	144
B291683		30	30	192
B291684		33	20	96
B291685		37	20	77
B291686		37	50	86
B291687		35	40	220
B291688		31	30	152
B291689				
B291690		168	<10	58
B291691		36	30	144
B291692		35	20	170
B291693		34	60	166
B291694		37	190	120
B291695		35	20	162
B291696		2	<10	8
B291697		35	30	172
B291698		36	30	68
B291699		33	30	63
B291700		35	30	59
B291701		23	30	40
B291702		25	20	40
B291703		31	30	321
B291704		34	20	418
B291705		32	10	216
B291706		33	40	556
B291707		31	40	909
B291708		35	30	574
B291709				
B291710		146	<10	92
B291711		31	20	443

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B291712		0.74	>10.0			9.69	1.7	1.14	476	70	<0.5	109	0.63	0.8	5	136
B291713		4.66	0.837				<0.5	6.99	353	1260	2.5	25	1.83	<0.5	7	148
B291714		4.28	0.587				<0.5	8.23	237	1560	3.2	5	2.27	<0.5	7	77
B291715		2.34	0.226				<0.5	7.59	382	1110	2.8	6	2.88	<0.5	8	106
B291716		1.54	<0.005				<0.5	0.12	<5	10	<0.5	<2	18.95	<0.5	<1	5
B291717		5.98	0.857				<0.5	7.69	163	1470	3.0	15	2.15	<0.5	8	110
B291718		5.72	1.100				<0.5	7.67	197	1530	3.2	20	1.90	<0.5	13	79
B291719		4.50	1.015				<0.5	7.60	294	1450	2.9	15	2.50	<0.5	7	124
B291720		6.38	0.527				<0.5	7.24	294	1500	2.7	34	1.92	<0.5	9	72
B291721		2.30	1.325				<0.5	7.24	320	1390	2.8	41	1.95	<0.5	11	122
B291722		2.16	0.816				<0.5	7.44	402	1540	2.8	13	2.00	<0.5	12	83
B291723		1.98	1.615				<0.5	7.00	542	1480	2.8	31	1.76	<0.5	10	125
B291724		2.08	0.387				<0.5	8.22	1320	1740	3.0	10	2.02	<0.5	21	83
B291725		3.28	0.321	0.242			1.3	7.19	494	700	2.8	5	2.61	3.2	7	119
B291726		5.76	1.425	1.380			<0.5	7.42	276	1580	3.0	23	2.35	<0.5	10	99
B291727		3.66	2.92				0.5	7.11	152	1490	2.9	59	2.42	<0.5	13	140
B291728		5.20	0.163	0.237			<0.5	7.71	164	1620	3.2	<2	2.45	<0.5	12	92
B291729			0.307	0.151												
B291730		0.10	0.987	1.020			2.2	7.31	14	450	0.7	<2	1.82	1.2	24	103
B291731		5.18	0.244	0.241			<0.5	7.34	67	1540	2.9	<2	2.24	<0.5	10	133
B291732		5.62	0.024				<0.5	7.50	38	1620	3.0	<2	2.39	<0.5	10	92
B291733		6.20	0.265				<0.5	7.26	32	1600	3.0	5	2.30	<0.5	10	128
B291734		6.46	0.428				<0.5	7.72	91	1640	3.1	10	2.24	<0.5	11	97
B291735		6.78	0.158				<0.5	7.54	75	1560	3.4	<2	2.27	<0.5	9	120
B291736		1.26	<0.005				<0.5	0.11	<5	20	<0.5	<2	20.2	<0.5	2	9
B291737		6.64	0.191				<0.5	7.86	51	1710	3.2	11	2.52	<0.5	10	127
B291738		6.48	0.148				<0.5	7.81	213	1760	3.0	2	2.64	<0.5	10	86
B291739		6.32	0.160				<0.5	7.60	16	1580	3.2	<2	2.40	<0.5	9	116
B291740		5.88	0.127				<0.5	7.53	103	1640	3.3	<2	2.42	<0.5	9	86
B291741		2.52	0.289				<0.5	7.34	82	1530	3.1	<2	2.15	<0.5	9	127
B291742		2.68	2.07				<0.5	7.20	140	1520	3.1	47	2.15	<0.5	11	93
B291743		5.00	0.174				<0.5	7.13	25	1460	3.1	<2	2.30	<0.5	10	143
B291744		5.74	0.084				<0.5	7.51	60	1640	3.2	3	2.41	<0.5	10	85
B291745		3.88	0.452				<0.5	7.05	105	1500	2.9	4	2.09	<0.5	10	130
B291746		2.58	0.378				1.3	7.06	222	650	3.2	<2	2.50	2.3	9	88
B291747		6.24	0.464				<0.5	7.30	94	1520	3.1	8	2.33	<0.5	11	133
B291748		5.20	0.123				<0.5	7.55	20	1560	3.3	2	2.24	<0.5	8	89
B291749			0.200													
B291750		0.10	0.416				3.0	9.54	<5	1170	1.3	<2	1.58	<0.5	9	10
B291750A		0.10	0.418				3.0	9.87	<5	1200	1.3	<2	1.64	<0.5	11	10

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B291712		92	1.32	0.02	0.45	0.06	139	3	0.01	14	80	133	0.20	68	33	0.04
B291713		51	2.16	0.05	3.03	0.55	204	6	1.11	21	530	26	0.09	18	362	0.26
B291714		28	2.22	0.04	3.86	0.67	227	3	1.76	21	630	23	0.04	6	501	0.31
B291715		37	2.19	0.03	3.29	0.47	300	3	1.28	22	630	25	0.08	9	356	0.30
B291716		1	0.09	<0.01	0.03	11.20	140	<1	0.01	5	500	<2	<0.01	<5	111	<0.01
B291717		41	2.24	0.02	3.74	0.68	220	2	1.60	22	600	23	0.06	<5	437	0.29
B291718		90	2.67	0.02	4.14	0.66	228	13	1.54	23	590	27	0.04	<5	416	0.29
B291719		35	2.14	0.02	3.64	0.69	237	2	1.65	20	570	23	0.02	6	466	0.28
B291720		54	2.30	0.02	3.92	0.73	202	9	1.58	22	590	34	0.16	8	447	0.29
B291721		43	2.28	0.02	3.27	0.67	218	2	1.49	21	580	52	0.10	15	417	0.28
B291722		49	2.44	0.03	3.62	0.71	217	2	1.57	23	600	35	0.10	11	442	0.29
B291723		39	2.14	0.03	3.66	0.61	240	2	1.37	20	570	58	0.04	29	346	0.27
B291724		97	2.72	0.01	4.40	0.82	237	4	1.54	24	690	26	0.33	11	469	0.33
B291725		50	2.36	0.10	3.22	0.52	1080	3	0.21	18	640	246	0.27	123	150	0.27
B291726		43	2.34	0.04	3.72	0.73	265	3	1.60	21	640	36	0.17	<5	449	0.31
B291727		85	2.47	0.01	3.66	0.74	232	4	1.55	24	610	26	0.42	<5	456	0.29
B291728		36	2.42	0.02	3.62	0.81	274	3	1.68	20	660	30	0.16	<5	483	0.32
B291729																
B291730		2040	4.88	0.02	1.68	1.27	409	2	2.93	51	640	25	0.62	<5	199	0.30
B291731		42	2.33	0.02	3.59	0.82	259	1	1.63	22	620	28	0.16	<5	450	0.30
B291732		25	2.41	0.02	3.46	0.82	293	1	1.70	21	640	29	0.10	<5	501	0.32
B291733		33	2.37	0.02	3.52	0.84	244	1	1.67	23	650	28	0.17	<5	480	0.32
B291734		42	2.56	0.08	3.68	0.87	263	7	1.66	23	620	25	0.18	<5	474	0.32
B291735		27	2.27	0.01	3.57	0.78	267	2	1.67	21	620	30	0.12	<5	468	0.30
B291736		2	0.12	<0.01	0.03	11.65	162	<1	0.01	2	550	2	0.02	<5	105	<0.01
B291737		31	2.45	0.01	3.65	0.84	273	3	1.79	22	670	29	0.14	<5	510	0.31
B291738		26	2.62	0.01	3.59	0.91	298	1	1.80	22	680	25	0.18	<5	519	0.33
B291739		22	2.38	0.01	3.41	0.82	275	4	1.72	21	660	28	0.14	<5	456	0.31
B291740		30	2.37	0.01	3.47	0.82	267	1	1.73	23	640	28	0.17	<5	481	0.31
B291741		36	2.23	0.01	3.58	0.82	263	1	1.64	18	610	34	0.13	5	450	0.30
B291742		35	2.27	0.01	3.66	0.79	252	1	1.63	22	610	30	0.17	6	442	0.30
B291743		30	2.38	0.06	3.34	0.84	315	2	1.58	22	620	32	0.11	5	418	0.30
B291744		28	2.40	0.03	3.63	0.83	303	1	1.69	23	660	30	0.11	<5	475	0.31
B291745		43	2.24	0.02	3.54	0.69	249	3	1.40	20	580	35	0.23	22	388	0.28
B291746		64	3.25	0.06	3.42	0.60	512	3	0.33	22	560	118	2.16	63	206	0.24
B291747		43	2.36	0.02	3.83	0.81	319	1	1.34	21	610	43	0.22	18	373	0.29
B291748		39	2.30	0.01	3.89	0.75	250	<1	1.67	20	620	34	0.17	10	447	0.29
B291749																
B291750		7720	3.41	0.03	3.76	1.19	505	2	3.40	12	2040	12	0.26	<5	700	0.36
B291750A		8150	3.53	0.03	3.94	1.23	524	3	3.57	9	2140	11	0.27	<5	732	0.37

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291712		5	20	79
B291713		31	30	55
B291714		36	20	65
B291715		36	30	74
B291716		2	<10	6
B291717		35	60	36
B291718		35	120	42
B291719		33	30	58
B291720		35	50	129
B291721		33	20	120
B291722		35	20	125
B291723		33	30	200
B291724		40	210	73
B291725		34	20	462
B291726		37	30	61
B291727		34	30	48
B291728		38	30	56
B291729				
B291730		90	<10	200
B291731		36	30	54
B291732		39	20	65
B291733		39	20	50
B291734		38	20	55
B291735		35	30	52
B291736		1	<10	7
B291737		38	10	58
B291738		40	60	55
B291739		36	10	48
B291740		37	<10	50
B291741		35	20	62
B291742		36	20	57
B291743		38	20	71
B291744		38	20	67
B291745		34	10	63
B291746		31	30	357
B291747		35	20	75
B291748		35	10	57
B291749				
B291750		182	10	60
B291750A		187	<10	56

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B291751		6.42	0.195				<0.5	7.45	341	1560	3.0	7	2.04	<0.5	11	93
B291752		3.52	0.640				<0.5	7.07	107	1660	2.8	2	2.04	<0.5	10	146
B291753		6.48	0.271				2.0	7.45	166	590	2.5	19	2.53	1.6	13	86
B291754		1.64	0.728				0.9	6.66	2120	590	2.4	12	2.53	4.6	15	139
B291755		5.60	0.240				0.6	7.46	65	690	3.2	<2	2.22	2.1	7	89
B291756		1.56	0.012				<0.5	0.18	8	30	<0.5	<2	21.8	<0.5	2	12
B291757		1.54	0.044				<0.5	6.94	56	880	4.0	<2	1.38	<0.5	6	87
B291758		5.56	0.136				<0.5	7.60	61	1450	4.0	2	2.15	<0.5	9	117
B291759		1.82	0.169				<0.5	6.87	59	1310	3.3	<2	2.23	<0.5	9	106
B291760		2.64	0.298				<0.5	7.65	54	1610	3.3	<2	2.47	<0.5	11	115
B291761		3.28	0.357				<0.5	7.43	56	1560	3.3	12	2.23	<0.5	12	107
B291762		3.18	0.238				<0.5	7.51	18	1640	3.1	2	2.26	<0.5	10	119
B291763		3.62	0.270				<0.5	7.36	32	1510	3.2	6	2.14	<0.5	9	94
B291764		3.54	0.491				<0.5	7.17	32	1480	2.9	8	1.98	<0.5	9	120
B291765		1.38	0.139				<0.5	5.66	284	780	2.6	5	1.90	<0.5	8	130
B291766		5.86	1.090				<0.5	6.31	43	1300	3.3	20	1.84	<0.5	7	94
B291767		4.14	0.957				<0.5	7.55	43	1490	3.2	11	2.21	<0.5	8	123
B291768		6.46	0.201				<0.5	7.44	199	1470	2.9	4	2.15	<0.5	7	90
B291769			0.310													
B291770		0.10	0.081				<0.5	7.37	106	590	2.7	<2	0.52	<0.5	57	1165
B291771		3.52	0.178				<0.5	7.77	108	1590	2.8	9	2.36	<0.5	8	120
B291772		6.44	0.163				<0.5	6.57	416	1320	2.2	7	1.84	<0.5	11	97
B291773		3.04	0.456				<0.5	7.20	217	1400	2.9	8	1.66	<0.5	9	126
B291774		3.62	0.239				0.8	7.32	1485	830	2.9	7	2.41	1.0	9	102
B291775		2.72	0.829				<0.5	7.75	31	1470	3.1	25	1.99	<0.5	8	114
B291776		1.90	<0.005				<0.5	0.11	<5	10	<0.5	<2	18.25	<0.5	<1	6
B291777		5.16	0.292				<0.5	6.76	65	1300	3.2	5	1.76	<0.5	8	118
B291778		5.70	0.376				<0.5	7.33	67	1520	3.2	<2	2.27	<0.5	9	78
B291779		7.70	0.166				<0.5	6.89	105	1390	2.9	8	1.98	<0.5	9	110
B291780		5.08	0.321				<0.5	6.98	69	1480	3.1	6	1.80	<0.5	9	86
B291781		2.06	0.749				<0.5	7.72	169	1640	2.8	8	2.36	<0.5	16	82
B291782		2.08	0.395				1.0	7.56	124	1580	2.7	7	2.64	<0.5	12	107
B291783		7.78	1.105				<0.5	6.84	38	1400	2.9	8	2.24	<0.5	8	80
B291784		6.88	0.204				<0.5	7.28	58	1440	3.1	9	2.05	<0.5	9	120
B291785		7.30	0.251				<0.5	7.30	155	1240	4.0	12	1.82	<0.5	16	89
B291786		6.78	0.899				<0.5	7.09	58	1510	3.3	14	2.16	<0.5	11	119
B291787		6.52	0.653				<0.5	6.99	150	1490	3.1	12	2.20	<0.5	9	91
B291788		6.10	0.191				<0.5	7.55	61	1380	3.1	3	2.14	<0.5	8	105
B291789			0.442													
B291790		0.10	0.368				2.8	8.82	<5	1000	1.2	<2	1.35	<0.5	9	7

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B291751		64	2.38	0.02	3.92	0.81	252	2	1.44	20	590	31	0.27	8	398	0.29
B291752		81	2.43	0.02	3.63	0.78	243	2	1.40	23	660	23	0.25	9	395	0.31
B291753		89	2.36	0.05	3.30	0.70	622	2	0.10	16	590	204	0.90	77	141	0.26
B291754		91	3.09	0.09	2.90	0.69	914	21	0.03	17	500	560	1.60	307	95	0.19
B291755		28	2.08	0.06	3.23	0.60	599	<1	0.55	17	540	84	0.66	42	163	0.23
B291756		4	0.14	0.01	0.08	12.00	168	<1	0.01	4	550	4	0.03	<5	115	<0.01
B291757		18	1.08	0.06	4.39	0.30	152	<1	1.50	10	230	36	0.08	<5	279	0.13
B291758		32	2.20	0.02	4.11	0.71	253	1	1.66	18	550	34	0.16	<5	395	0.27
B291759		23	2.10	0.01	3.55	0.64	285	2	1.54	20	530	33	0.18	<5	370	0.27
B291760		44	2.50	0.01	3.57	0.87	267	1	1.57	22	670	24	0.20	<5	456	0.32
B291761		40	2.37	0.01	4.01	0.76	233	1	1.63	20	620	28	0.20	<5	429	0.31
B291762		38	2.45	0.01	3.63	0.80	238	1	1.59	21	620	27	0.18	<5	429	0.30
B291763		23	2.45	0.01	3.67	0.82	286	1	1.65	22	620	22	0.11	<5	472	0.32
B291764		37	2.34	0.01	3.59	0.82	224	2	1.48	21	610	19	0.16	<5	438	0.29
B291765		33	0.86	0.02	4.93	0.23	124	<1	1.03	7	170	23	0.14	<5	295	0.09
B291766		22	2.13	0.01	3.56	0.72	272	1	1.64	16	540	25	0.10	<5	391	0.27
B291767		20	2.44	0.01	3.66	0.83	292	<1	1.74	18	630	27	0.09	10	455	0.29
B291768		20	2.33	0.01	3.50	0.82	309	1	1.54	19	590	24	0.10	6	427	0.27
B291769																
B291770		400	8.89	0.03	2.22	0.60	408	9	0.13	487	360	155	0.02	9	54	0.22
B291771		33	2.40	0.04	3.95	0.90	321	2	1.42	19	610	22	0.10	9	428	0.28
B291772		86	2.13	0.02	3.74	0.68	251	8	1.18	21	510	24	0.29	16	344	0.22
B291773		45	2.18	0.01	4.07	0.73	234	1	1.31	15	570	27	0.20	15	370	0.26
B291774		61	1.98	0.02	3.78	0.48	469	<1	0.25	21	570	92	0.43	44	172	0.25
B291775		25	2.40	0.01	3.79	0.77	266	<1	1.63	15	580	37	0.15	15	432	0.29
B291776		2	0.10	<0.01	0.03	10.85	154	<1	0.01	<1	470	2	<0.01	<5	106	<0.01
B291777		28	2.11	0.01	3.88	0.72	232	2	1.47	17	530	24	0.16	11	373	0.26
B291778		42	2.44	0.01	3.81	0.88	253	1	1.59	19	640	19	0.24	8	451	0.31
B291779		28	2.24	0.01	3.70	0.75	254	1	1.57	19	580	24	0.14	6	423	0.29
B291780		36	2.26	0.01	3.81	0.80	247	1	1.43	19	580	23	0.16	14	377	0.28
B291781		65	2.57	0.01	4.56	0.83	276	12	1.45	20	640	19	0.30	9	473	0.30
B291782		75	2.49	0.01	4.58	0.83	291	29	1.35	20	620	18	0.29	12	473	0.31
B291783		32	2.32	0.01	3.79	0.79	286	1	1.46	19	570	21	0.10	14	430	0.29
B291784		29	2.32	0.01	3.95	0.79	269	1	1.66	18	590	23	0.14	6	439	0.30
B291785		54	2.00	0.01	4.56	0.69	157	1	1.66	18	490	19	0.24	5	396	0.26
B291786		41	2.40	0.01	4.07	0.83	221	2	1.65	20	600	22	0.20	<5	465	0.31
B291787		54	2.35	0.03	3.82	0.82	200	4	1.60	17	600	18	0.23	8	489	0.31
B291788		69	2.25	0.03	3.94	0.79	170	1	1.67	18	630	15	0.30	<5	498	0.30
B291789																
B291790		7530	3.11	0.03	3.77	1.11	476	2	3.24	9	1880	6	0.23	<5	672	0.33

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B291751		35	20	47
B291752		38	20	112
B291753		35	30	250
B291754		26	30	748
B291755		30	20	370
B291756		2	<10	11
B291757		14	20	23
B291758		33	30	49
B291759		32	10	56
B291760		40	10	54
B291761		37	30	48
B291762		36	20	48
B291763		40	120	59
B291764		37	30	42
B291765		11	20	10
B291766		32	20	55
B291767		36	30	60
B291768		33	20	61
B291769				
B291770		93	30	601
B291771		35	20	56
B291772		28	20	45
B291773		33	20	49
B291774		33	30	165
B291775		37	20	49
B291776		1	<10	6
B291777		32	20	45
B291778		39	30	45
B291779		36	10	48
B291780		35	20	48
B291781		38	130	44
B291782		39	240	44
B291783		36	20	55
B291784		37	20	56
B291785		31	20	22
B291786		38	20	37
B291787		39	20	31
B291788		37	30	22
B291789				
B291790		172	<10	55

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B291791		2.92	0.301				<0.5	7.04	63	1500	3.1	4	1.94	<0.5	9	84
B291792		4.06	7.76				10.8	4.50	>10000	490	1.9	212	1.12	1.4	61	158
B291793		2.10	9.37				4.4	6.77	>10000	640	2.8	255	1.54	2.3	64	106
B291794		3.24	0.169				<0.5	7.45	196	1500	3.1	5	2.02	0.7	11	115
B291795		3.18	0.373				0.7	6.91	186	1410	2.9	10	2.18	2.2	11	91
B291796		1.66	0.030				<0.5	0.48	27	70	<0.5	<2	17.85	<0.5	<1	10
B291797		2.28	2.13				1.9	6.90	30	1280	2.9	36	2.37	0.8	8	90
B291798		3.78	0.136				0.6	7.04	55	1500	3.0	4	2.70	<0.5	10	108
B291799		1.02	0.473				0.8	6.94	116	1540	4.0	5	1.50	3.4	7	81
B291800		0.86	1.645				7.4	4.90	233	250	1.7	35	0.28	7.0	8	160
B291801		2.68	0.393				0.6	7.49	66	1610	3.1	5	2.01	<0.5	10	92
B291802		2.66	0.562				1.4	8.13	39	1660	3.2	11	1.97	<0.5	9	112
B291803		5.40	0.868				7.8	6.91	6230	390	2.6	21	2.44	5.8	15	97
B291804		3.56	0.135	0.089	0.180		0.7	7.30	43	1440	3.4	2	2.16	<0.5	8	105
B291805		5.60	0.280	0.357	0.607		0.7	8.02	797	1440	3.3	9	2.46	0.5	18	113
B291806		7.04	0.398	0.408	0.138		<0.5	6.88	25	1270	3.0	7	2.36	<0.5	9	39
B291807		5.48	0.037				<0.5	7.38	46	1280	3.4	<2	2.36	<0.5	8	104
B291808		6.78	0.166				1.7	7.49	49	950	3.1	2	2.98	22.8	8	92
B291809			0.138													
B291810		0.10	3.02				1.7	6.72	8	1930	3.3	<2	4.36	<0.5	25	134
B291811		3.28	0.107				0.5	7.00	21	1320	3.3	<2	2.67	1.9	8	104
B291812		5.52	0.057				<0.5	6.93	94	1310	3.2	<2	2.35	0.6	9	100
B291813		2.24	0.022				<0.5	7.53	53	1430	3.2	<2	2.34	<0.5	9	114
B291814		4.68	4.49				3.8	6.82	1250	1200	2.7	98	1.38	0.6	11	109
B291815		4.96	0.063				<0.5	7.02	56	1190	3.2	<2	2.26	<0.5	8	119
B291816		1.72	<0.005				<0.5	0.15	<5	20	<0.5	<2	18.20	<0.5	1	7
B291817		6.82	0.052				<0.5	7.29	76	1240	3.2	<2	2.59	<0.5	10	111
B291818		6.24	0.072				<0.5	7.55	44	1260	3.1	<2	2.71	<0.5	8	85
B291819		5.96	0.857				<0.5	8.04	44	1440	3.3	2	2.75	<0.5	9	112
B291820		6.30	0.414				0.6	7.63	600	1420	3.1	7	2.54	<0.5	20	96
B291821		2.86	3.38				0.7	7.48	51	1340	3.1	67	2.59	<0.5	11	126
B291822		3.10	1.130				<0.5	7.56	37	1350	3.1	29	2.60	<0.5	11	106
B291823		7.34	0.208				<0.5	7.83	69	1400	3.3	3	2.87	<0.5	10	126

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01
B291791		83	2.30	0.01	4.26	0.72	180	1	1.42	17	610	24	0.38	14	417	0.29
B291792		146	2.92	0.01	2.47	0.32	331	2	0.25	12	280	1115	1.64	611	101	0.13
B291793		236	3.73	<0.01	3.84	0.64	537	1	0.36	14	540	545	1.96	232	152	0.24
B291794		52	2.85	0.01	4.08	0.76	398	1	1.14	22	650	124	0.64	58	339	0.31
B291795		72	2.76	0.03	4.10	0.75	360	3	1.03	18	630	114	0.70	56	322	0.29
B291796		4	0.21	<0.01	0.22	10.65	150	<1	0.06	1	540	3	0.03	5	118	0.01
B291797		68	2.31	0.02	4.09	0.69	387	2	1.03	17	600	173	0.45	63	297	0.29
B291798		61	2.40	0.01	3.85	0.86	359	1	1.44	15	610	24	0.19	18	457	0.30
B291799		70	2.13	0.06	4.07	0.65	236	2	0.74	16	550	168	0.53	49	257	0.27
B291800		298	2.72	0.11	2.57	0.16	51	<1	0.07	4	40	404	2.69	162	38	0.03
B291801		64	2.43	0.01	3.92	0.76	197	1	1.54	16	680	33	0.34	19	430	0.30
B291802		73	2.47	0.01	4.00	0.78	186	<1	1.52	20	670	20	0.35	20	436	0.30
B291803		146	4.56	0.07	3.22	0.80	1225	<1	0.16	15	550	553	2.80	314	138	0.23
B291804		65	2.41	0.01	3.79	0.87	220	<1	1.65	14	620	19	0.29	6	489	0.30
B291805		102	2.91	0.01	3.93	1.06	296	1	1.62	14	650	59	0.46	24	508	0.31
B291806		37	2.57	0.01	3.57	1.02	332	1	1.59	9	600	27	0.17	6	467	0.29
B291807		34	2.39	0.01	3.62	0.98	309	2	1.65	10	590	24	0.16	<5	470	0.28
B291808		67	3.36	0.35	3.65	1.08	1125	4	0.46	10	650	423	1.02	137	241	0.28
B291809																
B291810		106	4.84	<0.01	3.41	2.75	1030	12	2.14	63	2150	28	0.29	<5	1565	0.38
B291811		33	2.62	0.04	3.66	0.91	640	1	0.83	14	660	102	0.19	32	323	0.30
B291812		58	2.56	0.02	3.80	0.96	331	3	1.37	13	590	22	0.38	20	389	0.29
B291813		34	2.57	0.01	3.73	1.04	377	<1	1.64	17	640	28	0.15	9	490	0.31
B291814		57	2.36	0.01	3.53	0.92	310	3	1.18	11	560	459	0.35	285	307	0.26
B291815		35	2.41	0.01	3.81	0.96	369	<1	1.54	11	580	27	0.19	8	428	0.28
B291816		2	0.12	<0.01	0.05	10.85	158	<1	0.03	3	470	3	0.01	<5	110	<0.01
B291817		48	2.59	0.01	3.90	1.08	352	8	1.56	12	620	23	0.29	10	439	0.29
B291818		33	2.56	0.01	3.59	1.13	371	2	1.69	13	610	19	0.15	5	506	0.29
B291819		28	2.69	<0.01	3.76	1.06	396	2	1.70	17	650	33	0.16	7	526	0.31
B291820		87	2.93	<0.01	4.14	1.16	293	1	1.65	13	690	22	0.42	9	538	0.31
B291821		54	2.86	<0.01	3.73	1.25	336	3	1.69	13	660	19	0.24	6	564	0.30
B291822		65	2.93	<0.01	3.79	1.26	339	2	1.65	10	670	18	0.30	<5	559	0.31
B291823		51	3.01	<0.01	3.63	1.28	386	6	1.73	10	690	17	0.26	<5	572	0.32

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05046971

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	V	W	Zn
	Units	ppm	ppm	ppm
	LOR	1	10	2
B291791		37	30	28
B291792		18	110	190
B291793		33	40	371
B291794		41	20	106
B291795		37	30	407
B291796		3	<10	23
B291797		37	20	117
B291798		37	20	64
B291799		33	20	491
B291800		5	60	1085
B291801		39	20	37
B291802		38	10	32
B291803		34	30	920
B291804		43	10	27
B291805		53	40	87
B291806		50	20	55
B291807		48	10	46
B291808		51	30	3630
B291809				
B291810		166	10	99
B291811		51	10	321
B291812		50	30	128
B291813		50	20	51
B291814		43	20	74
B291815		49	10	56
B291816		2	<10	7
B291817		54	10	44
B291818		52	10	40
B291819		53	20	51
B291820		57	110	34
B291821		59	60	39
B291822		59	50	37
B291823		60	40	46

Comments: ** CORRECTED COPY for sample type ** Additional Au-AA23 data for B291725: 0.267 ppm; B291728: 0.337 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Dat 2-OCT-2005
Account: STRGOL

CERTIFICATE VA05047189

Project: Dublin Gulch-1735

P.O. No.:

This report is for 59 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Pb-AA62	Ore grade Pb - four acid / AAS	AAS
Ag-AA62	Ore grade Ag - four acid /AAS	AAS

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: Robert Rogers

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292501		1.48	0.088	<0.5	7.24	1550	1540	2.9	5	1.94	<0.5	6	88	42	2.28	<0.01
B292502		1.80	0.062	<0.5	7.97	1340	1610	3.2	5	2.01	<0.5	7	30	40	2.34	<0.01
B292503		4.40	0.102	3.5	8.07	1915	1600	3.1	8	2.25	<0.5	6	31	63	2.43	<0.01
B292504		5.54	0.143	<0.5	7.55	3010	1560	3.0	16	1.70	<0.5	6	28	43	2.15	<0.01
B292505		4.60	0.199	<0.5	7.68	3010	1470	3.1	16	1.80	<0.5	8	28	51	2.30	<0.01
B292506		3.34	1.020	>100	7.68	5380	1540	3.0	85	2.11	<0.5	8	27	595	2.65	0.01
B292507		3.96	0.332	18.6	7.86	2810	1590	3.0	16	2.07	<0.5	8	33	126	2.46	<0.01
B292508		2.96	0.430	2.8	6.80	4620	1480	2.9	17	1.94	<0.5	8	24	77	2.28	<0.01
B292509			0.509													
B292510		0.10	2.65	<0.5	7.82	2070	780	13.6	<2	0.02	<0.5	1	147	104	3.53	0.07
B292511		4.00	0.122	<0.5	7.71	1925	1660	3.1	6	2.13	<0.5	8	28	56	2.31	<0.01
B292512		1.38	0.161	<0.5	6.96	4780	1460	2.9	28	1.90	<0.5	8	52	69	2.29	<0.01
B292513		5.12	0.332	1.9	7.42	4110	1520	3.2	21	2.09	<0.5	8	57	76	2.33	<0.01
B292514		4.56	0.276	<0.5	6.81	4830	1430	3.1	17	2.23	<0.5	8	52	71	2.19	<0.01
B292515		5.88	0.145	<0.5	7.57	2270	1380	3.0	15	2.14	<0.5	7	53	68	2.09	0.01
B292516		1.42	<0.005	<0.5	0.11	8	10	<0.5	<2	18.95	<0.5	1	4	1	0.10	<0.01
B292517		5.44	0.450	<0.5	7.29	7890	1360	2.6	38	2.34	<0.5	11	58	54	2.49	<0.01
B292518		7.74	0.231	0.5	6.69	4230	1390	2.8	20	2.31	0.9	8	51	67	2.30	0.02
B292519		5.88	0.336	<0.5	7.35	5720	1480	3.2	23	1.96	<0.5	11	59	93	2.42	0.01
B292520		5.20	0.241	1.6	7.14	3540	1040	2.5	25	1.66	1.6	8	62	92	2.48	0.05
B292521		2.98	0.208	0.7	7.76	3750	1220	2.9	23	1.72	<0.5	9	55	89	2.98	0.02
B292522		3.42	0.283	0.7	6.93	4870	1130	2.7	20	1.76	<0.5	8	54	77	2.73	0.04
B292523		2.78	0.418	<0.5	7.49	7810	1560	2.4	30	1.64	<0.5	8	55	66	2.45	0.02
B292524		3.32	0.503	<0.5	6.97	5580	1350	2.6	35	2.54	<0.5	8	42	83	2.19	0.03
B292525		5.48	0.299	<0.5	6.93	3250	1380	2.7	15	2.18	<0.5	8	50	82	2.16	0.02
B292526		4.62	0.483	<0.5	7.34	5010	1400	3.1	26	2.20	<0.5	10	49	58	2.45	0.01
B292527		1.46	0.169	<0.5	6.47	2600	1140	2.4	8	3.81	<0.5	6	41	62	2.13	0.02
B292528		6.42	0.263	<0.5	7.64	3940	1520	3.2	30	2.06	<0.5	9	47	65	2.39	0.01
B292529			0.261													
B292530		0.10	1.250	<0.5	6.86	1250	700	6.1	3	0.02	<0.5	6	212	40	3.67	0.05
B292531		5.96	0.257	<0.5	7.43	4280	1260	3.1	17	2.21	<0.5	9	47	50	2.51	0.01
B292532		5.36	0.191	0.9	7.32	4030	1300	3.0	16	1.96	1.8	8	45	41	2.54	0.03
B292533		1.36	0.249	2.8	2.60	2280	170	1.2	11	7.46	3.5	3	17	16	10.90	0.12
B292534		3.32	0.166	3.2	7.46	4240	460	2.8	14	1.90	12.8	7	57	83	2.54	0.31
B292535		2.90	0.050	0.8	6.79	1235	610	2.4	2	2.32	6.1	6	42	33	2.86	0.12
B292536		1.40	<0.005	<0.5	0.15	<5	20	<0.5	<2	19.25	<0.5	1	7	2	0.13	<0.01
B292537		5.78	0.103	<0.5	7.48	2340	1170	2.7	8	1.83	1.0	8	46	44	2.52	0.03
B292538		2.82	0.115	<0.5	7.48	4040	1370	3.0	12	1.61	<0.5	9	46	74	2.40	0.01
B292539		4.48	0.157	1.6	7.39	3770	1120	2.9	11	1.97	2.1	8	47	58	2.63	0.05
B292540		5.42	0.162	<0.5	7.80	5300	1550	3.2	15	1.61	<0.5	11	45	63	2.67	0.01

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292501		3.68	0.67	176	2	1.65	20	620	20	0.02	<5	470	0.29	37	<10	24
B292502		3.85	0.71	183	2	1.74	20	650	20	0.01	<5	498	0.31	39	<10	26
B292503		3.88	0.71	175	9	1.64	19	630	16	0.02	<5	485	0.30	40	20	27
B292504		4.17	0.62	143	2	1.60	17	590	15	0.06	<5	458	0.28	36	10	17
B292505		3.88	0.61	161	2	1.72	20	600	20	0.05	5	444	0.29	39	<10	25
B292506		3.68	0.74	189	388	1.46	56	600	16	0.18	12	437	0.29	36	2300	28
B292507		4.28	0.84	168	6	1.40	21	630	12	0.10	<5	439	0.30	42	30	20
B292508		3.88	0.82	133	3	1.34	21	600	14	0.23	6	391	0.27	34	10	15
B292509																
B292510		3.21	0.40	73	3	0.09	12	330	29	0.02	158	145	0.24	106	20	15
B292511		4.05	0.73	159	2	1.41	20	630	12	0.36	5	397	0.30	38	<10	18
B292512		4.02	0.68	136	1	1.15	20	590	18	0.56	7	325	0.28	36	10	17
B292513		4.34	0.77	131	3	1.49	20	590	23	0.54	<5	413	0.28	36	30	51
B292514		4.37	0.73	119	4	1.45	17	560	17	0.54	<5	393	0.27	35	20	18
B292515		4.23	0.67	147	2	1.23	18	550	20	0.42	<5	324	0.26	34	10	22
B292516		0.03	11.45	136	<1	0.01	3	520	<2	0.01	<5	110	<0.01	2	<10	7
B292517		3.92	0.79	184	1	1.04	22	590	24	0.65	12	314	0.26	34	30	27
B292518		3.92	0.73	364	2	1.08	17	580	93	0.51	25	353	0.27	36	20	186
B292519		4.71	0.73	238	2	1.08	22	700	24	0.63	21	351	0.32	42	30	53
B292520		4.14	0.65	672	2	0.39	20	590	102	0.41	57	177	0.26	35	30	360
B292521		4.19	0.83	501	3	0.25	24	640	65	0.37	57	199	0.29	38	30	324
B292522		4.13	0.75	485	3	0.29	20	620	55	0.41	43	198	0.27	36	30	229
B292523		4.24	0.55	253	3	0.61	24	620	16	0.50	31	251	0.28	35	30	84
B292524		4.25	0.64	424	4	0.43	19	590	23	0.53	25	247	0.27	35	30	92
B292525		4.28	0.72	392	1	0.66	18	580	26	0.48	17	302	0.27	35	20	36
B292526		4.56	0.61	269	3	1.10	20	560	19	0.52	10	364	0.26	35	20	18
B292527		4.22	0.78	546	1	0.59	14	540	65	0.50	17	292	0.24	32	20	88
B292528		4.31	0.71	207	1	1.35	16	580	22	0.48	8	417	0.28	36	20	22
B292529																
B292530		2.76	0.35	88	3	0.11	19	320	27	0.02	115	92	0.23	92	10	44
B292531		4.11	0.79	482	1	0.93	19	580	43	0.47	18	296	0.26	34	10	95
B292532		4.10	0.69	559	2	0.99	19	590	143	0.44	27	307	0.27	35	20	354
B292533		1.20	2.66	14100	1	0.03	6	190	>10000	2.14	5720	303	0.07	14	10	616
B292534		3.20	0.79	1555	2	0.02	17	580	476	0.61	153	80	0.24	35	20	1825
B292535		3.27	0.91	2420	2	0.07	14	540	768	0.43	258	116	0.24	31	20	935
B292536		0.03	11.70	156	<1	0.01	1	540	<2	0.01	<5	112	0.01	2	<10	8
B292537		4.19	0.80	834	4	0.30	21	630	104	0.41	27	204	0.28	37	20	200
B292538		4.50	0.69	326	9	0.78	18	610	16	0.49	16	287	0.28	37	30	17
B292539		3.87	0.83	778	5	0.53	16	570	146	0.39	32	231	0.27	36	20	349
B292540		4.39	0.71	275	2	1.04	20	630	15	0.48	12	330	0.30	39	20	20

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method / Analyte / Units / LOR	Pb-AA62 Pb % 0.01	Ag-AA62 Ag ppm 1
B292501			
B292502			
B292503			
B292504			
B292505			
B292506			125
B292507			
B292508			
B292509			
B292510			
B292511			
B292512			
B292513			
B292514			
B292515			
B292516			
B292517			
B292518			
B292519			
B292520			
B292521			
B292522			
B292523			
B292524			
B292525			
B292526			
B292527			
B292528			
B292529			
B292530			
B292531			
B292532			
B292533		1.23	
B292534			
B292535			
B292536			
B292537			
B292538			
B292539			
B292540			

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B292541		2.18	0.096	1.5	7.52	2560	1200	2.9	5	1.86	2.5	10	47	70	2.65	0.05
B292542		2.24	0.110	0.8	7.36	3170	1170	2.8	8	2.38	1.8	13	47	82	2.88	0.05
B292543		5.30	0.072	0.9	6.81	3200	420	2.5	16	2.50	5.5	8	57	171	2.90	0.10
B292544		2.56	0.085	<0.5	7.78	2220	1540	3.1	10	2.02	<0.5	9	43	84	2.62	0.01
B292545		5.82	0.052	1.2	7.85	1720	1480	2.9	7	2.34	1.6	11	50	99	2.44	0.08
B292546		4.98	0.049	<0.5	7.64	1550	1440	3.1	3	2.05	<0.5	9	49	74	2.50	0.01
B292547		5.10	0.074	<0.5	7.41	2000	1560	2.9	13	2.21	<0.5	10	50	89	2.38	0.01
B292548		4.86	0.041	0.6	7.67	2300	1330	3.0	11	2.58	<0.5	10	56	52	2.44	0.01
B292549			0.041													
B292550		0.10	2.87	1.5	7.19	<5	2080	3.2	<2	4.60	<0.5	25	138	99	5.09	0.01
B292551		1.82	0.025	<0.5	8.04	1455	1780	3.1	5	1.98	<0.5	9	61	56	2.63	0.01
B292552		4.26	0.149	2.6	6.43	2380	550	2.4	20	2.63	2.5	8	51	45	3.41	0.06
B292553		4.74	0.128	4.6	7.30	2830	480	2.7	16	3.77	10.2	9	55	68	3.74	0.25
B292554		3.34	0.067	0.6	7.49	2340	1260	2.8	13	1.18	1.4	9	55	50	2.92	0.03
B292555		2.40	0.067	0.8	8.20	1400	1060	3.1	11	1.22	2.7	9	63	51	2.84	0.04
B292556		1.76	<0.005	<0.5	0.15	5	10	<0.5	<2	19.45	<0.5	<1	3	2	0.10	<0.01
B292557		6.24	0.037	1.2	8.07	2810	1120	2.8	6	1.72	1.4	9	53	47	2.70	0.03
B292558		4.48	0.012	<0.5	8.26	676	1680	3.3	<2	1.82	<0.5	9	55	37	2.99	<0.01
B292559		1.50	0.008	<0.5	7.81	472	1320	3.5	<2	3.04	<0.5	8	41	34	1.76	0.01

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292541		4.07	0.73	826	3	0.63	16	580	265	0.61	20	261	0.27	37	30	369
B292542		4.11	0.79	1115	2	0.57	15	580	98	0.71	24	269	0.27	36	10	311
B292543		2.99	0.91	1770	2	0.16	18	540	203	1.04	54	153	0.24	36	30	800
B292544		4.11	0.74	306	2	0.88	21	630	14	0.41	14	315	0.29	38	10	21
B292545		4.29	0.71	369	3	0.93	19	620	85	0.57	13	323	0.28	37	20	242
B292546		3.94	0.75	331	2	1.19	17	610	46	0.42	5	366	0.28	37	10	75
B292547		4.32	0.78	283	4	1.17	19	630	24	0.40	10	383	0.29	38	20	36
B292548		3.91	0.74	506	3	1.15	19	630	45	0.40	10	368	0.27	38	10	94
B292549																
B292550		3.35	2.94	1060	13	2.27	61	2350	30	0.30	<5	1600	0.35	156	10	92
B292551		4.10	0.76	290	2	1.43	20	720	19	0.29	14	429	0.32	39	20	31
B292552		3.02	0.86	1850	2	0.17	15	520	154	1.62	35	152	0.21	29	20	376
B292553		3.08	1.11	2110	2	0.04	18	570	484	1.70	33	148	0.22	32	30	1510
B292554		4.22	0.89	380	4	0.39	19	590	64	0.32	8	215	0.27	35	10	244
B292555		3.80	0.89	572	5	0.35	12	650	166	0.33	14	179	0.28	37	20	409
B292556		0.05	11.65	149	<1	0.02	<1	520	<2	<0.01	<5	108	<0.01	1	<10	7
B292557		4.06	0.70	644	2	0.47	19	660	152	0.89	23	187	0.28	37	20	252
B292558		3.82	0.93	276	1	1.13	16	650	29	0.21	<5	377	0.31	39	10	50
B292559		3.85	0.57	370	2	0.56	14	600	31	0.22	<5	280	0.29	39	20	55

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 12-OCT-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047189

Sample Description	Method / Analyte / Units / LOR	Pb-AA62 Pb % 0.01	Ag-AA62 Ag ppm 1
B292541			
B292542			
B292543			
B292544			
B292545			
B292546			
B292547			
B292548			
B292549			
B292550			
B292551			
B292552			
B292553			
B292554			
B292555			
B292556			
B292557			
B292558			
B292559			

Comments: ** CORRECTED COPY for sample type **

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da(.9-JUN-2005
Account: STRGOL

CERTIFICATE VA05047825

Project: Dublin Gulch-1735

P.O. No.:

This report is for 148 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 17-JUN-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Pb-AA62	Ore grade Pb - four acid / AAS	AAS



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292560		5.14	0.028	<0.5	7.35	1495	1390	3.6	3	2.23	<0.5	8	52	48	2.37	0.01
B292561		2.94	0.061	0.6	7.69	1405	1350	4.0	11	1.63	<0.5	8	55	24	2.51	0.02
B292562		2.86	0.039	0.8	7.69	1105	1290	3.9	8	1.71	0.6	7	51	25	2.63	0.03
B292563		5.68	0.037	<0.5	7.81	1250	1480	3.4	11	2.59	<0.5	8	57	38	2.47	0.02
B292564		3.46	0.035	0.5	7.17	1935	1340	3.4	6	1.87	<0.5	7	48	50	2.54	0.01
B292565		5.56	0.032	1.2	7.07	1660	700	3.0	5	2.04	2.1	6	51	62	2.05	0.04
B292566		1.10	0.076	4.1	6.90	1620	510	2.7	15	3.16	8.9	6	57	45	2.87	0.13
B292567		4.02	0.043	<0.5	7.59	1155	1380	3.5	12	2.26	<0.5	6	106	68	2.32	0.01
B292568		5.42	0.049	<0.5	7.48	2110	1340	3.7	7	2.22	<0.5	8	72	54	2.16	0.01
B292569		<0.02	0.059													
B292570		0.10	0.087	<0.5	6.80	114	600	2.7	<2	0.54	<0.5	59	1200	400	8.60	0.03
B292571		5.24	0.031	<0.5	7.33	1940	1410	3.6	7	2.00	<0.5	9	105	64	2.30	<0.01
B292572		2.94	0.028	<0.5	7.39	1780	1360	3.3	4	2.53	<0.5	9	84	58	2.49	0.01
B292573		2.50	0.032	<0.5	7.32	832	1420	3.0	4	2.14	<0.5	8	106	64	2.19	0.01
B292574		4.52	0.034	<0.5	7.40	1315	1550	3.1	6	1.95	<0.5	8	79	73	2.90	0.01
B292575		6.12	0.037	<0.5	7.39	1035	1460	3.5	6	2.16	<0.5	8	102	73	2.42	<0.01
B292576		1.78	<0.005	<0.5	0.15	<5	20	<0.5	<2	19.10	<0.5	<1	8	2	0.12	<0.01
B292577		4.06	0.049	<0.5	7.71	2010	1340	3.5	5	2.55	<0.5	7	116	53	2.53	0.02
B292578		2.88	0.054	<0.5	7.52	3080	1450	3.5	10	2.21	<0.5	9	84	78	2.73	0.01
B292579		3.80	0.072	0.8	7.01	4680	620	2.9	8	2.92	1.1	7	93	39	2.41	0.03
B292580		2.68	0.068	0.5	7.27	4050	1020	3.1	13	2.10	<0.5	8	90	75	2.79	0.01
B292581		1.66	0.079	<0.5	7.26	4310	1400	3.5	15	1.90	<0.5	7	106	79	2.31	0.01
B292582		1.26	0.112	<0.5	7.27	4860	1380	3.3	17	1.98	<0.5	10	86	82	2.51	0.01
B292583		6.32	0.079	<0.5	7.23	3020	1470	3.4	9	2.30	<0.5	7	95	70	2.33	0.01
B292584		5.94	0.073	<0.5	7.63	2950	1390	3.4	9	2.08	<0.5	7	88	60	2.04	<0.01
B292585		5.00	0.082	<0.5	7.19	2030	1320	3.5	11	2.23	<0.5	8	130	59	2.08	<0.01
B292586		6.34	0.086	<0.5	7.23	2520	1220	3.4	10	2.16	<0.5	8	106	69	2.26	0.01
B292587		3.28	0.065	<0.5	7.20	1195	1000	3.1	14	2.16	<0.5	7	120	65	2.19	0.01
B292588		3.70	0.076	<0.5	7.26	1980	1290	3.3	8	1.88	<0.5	8	85	67	2.19	0.01
B292589		<0.02	0.075													
B292590		0.10	1.460	<0.5	6.70	1240	680	5.5	<2	0.01	<0.5	6	212	38	3.62	0.06
B292591		4.66	0.075	<0.5	7.56	1675	1340	3.6	7	1.88	<0.5	10	111	50	2.05	0.01
B292592		5.60	0.119	<0.5	7.53	1885	1370	3.5	8	2.06	<0.5	8	91	73	2.30	0.01
B292593		6.22	0.092	<0.5	7.28	1650	1400	3.2	4	2.08	<0.5	7	100	128	2.02	0.01
B292594		4.44	0.145	<0.5	7.32	1485	1470	2.9	6	1.61	<0.5	8	78	74	2.05	0.01
B292595		9.60	0.051	<0.5	7.63	1620	1400	3.4	6	2.26	<0.5	8	116	73	2.24	0.01
B292596		1.80	<0.005	<0.5	0.13	<5	30	<0.5	<2	20.2	<0.5	<1	9	3	0.12	<0.01
B292597		4.88	0.052	<0.5	7.57	1845	1440	3.3	10	2.01	<0.5	8	99	72	2.21	<0.01
B292598		2.76	0.065	<0.5	7.75	2200	1500	3.5	11	2.08	<0.5	9	102	87	2.29	<0.01
B292599		2.56	0.115	<0.5	7.60	3140	1480	3.3	32	2.04	<0.5	9	125	90	2.09	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292560		3.95	0.75	291	1	1.17	16	600	146	0.26	<5	361	0.28	38	10	36
B292561		3.84	0.79	307	2	1.13	14	620	76	0.20	7	337	0.29	40	10	95
B292562		3.64	0.83	441	2	1.07	14	600	96	0.27	6	317	0.28	40	10	139
B292563		3.65	0.81	295	2	1.40	18	620	47	0.30	<5	434	0.29	40	10	58
B292564		4.20	0.85	243	1	1.06	14	570	40	0.28	<5	354	0.26	37	10	29
B292565		3.64	0.97	518	1	0.21	14	550	68	0.50	15	160	0.23	35	10	319
B292566		3.20	0.96	1535	1	0.03	11	510	259	0.98	23	110	0.21	34	10	1215
B292567		4.22	0.87	225	2	1.38	15	610	33	0.34	<5	446	0.29	41	10	27
B292568		4.04	0.82	203	1	1.48	14	580	25	0.33	<5	436	0.27	38	10	26
B292569																
B292570		2.22	0.60	380	9	0.12	477	370	150	0.02	14	51	0.22	93	30	593
B292571		4.19	0.87	177	2	1.56	15	590	22	0.32	<5	463	0.28	38	10	27
B292572		3.99	0.90	250	2	1.16	17	600	19	0.63	6	419	0.28	37	10	36
B292573		3.91	1.02	211	1	0.87	17	600	17	0.37	5	393	0.28	38	10	21
B292574		4.19	1.04	210	1	0.74	16	630	17	0.84	8	346	0.29	39	10	22
B292575		4.04	0.91	200	1	1.53	17	630	19	0.35	<5	477	0.30	42	10	23
B292576		0.04	11.50	142	<1	0.02	2	570	3	0.01	<5	108	0.01	3	<10	6
B292577		4.12	0.91	353	1	1.19	15	610	34	0.36	6	397	0.28	42	10	84
B292578		4.31	0.98	348	1	1.14	15	660	27	0.43	9	382	0.30	43	10	30
B292579		3.60	1.10	1555	2	0.18	13	570	56	0.45	11	137	0.22	34	20	192
B292580		4.36	0.81	773	1	0.43	14	610	36	0.75	12	216	0.26	39	10	44
B292581		4.65	0.72	171	1	1.07	15	630	18	0.43	7	365	0.29	44	10	15
B292582		4.61	0.74	178	1	0.99	15	600	16	0.52	5	351	0.28	42	20	12
B292583		4.29	0.99	223	2	1.27	15	630	17	0.44	6	454	0.29	41	10	14
B292584		4.28	0.77	156	1	1.37	15	580	18	0.37	<5	447	0.27	39	10	17
B292585		4.46	0.76	194	1	1.52	15	560	21	0.36	<5	461	0.27	37	10	42
B292586		4.06	0.78	174	1	1.53	17	560	18	0.47	<5	429	0.27	39	10	49
B292587		3.76	0.94	160	1	1.42	16	590	11	0.47	<5	351	0.25	37	10	22
B292588		4.27	0.90	148	2	1.56	14	580	8	0.49	<5	453	0.28	40	10	21
B292589																
B292590		2.61	0.34	83	2	0.10	16	300	18	0.02	113	89	0.19	86	<10	43
B292591		4.45	0.93	166	2	1.75	15	560	11	0.25	<5	476	0.28	40	10	26
B292592		4.09	0.87	162	1	1.64	17	590	14	0.52	5	453	0.28	40	10	24
B292593		4.16	0.84	154	2	1.58	19	590	14	0.32	8	428	0.30	37	10	18
B292594		3.76	0.97	137	1	1.69	19	600	6	0.28	<5	440	0.29	36	10	17
B292595		3.95	0.95	161	1	1.75	18	590	9	0.30	<5	497	0.29	41	10	18
B292596		0.03	11.80	152	<1	0.01	7	500	2	0.02	<5	114	0.01	3	<10	8
B292597		4.03	0.93	149	<1	1.79	17	600	10	0.43	<5	496	0.30	40	10	16
B292598		4.23	1.01	136	1	1.71	20	620	8	0.41	<5	497	0.31	43	20	16
B292599		4.42	0.74	122	2	1.86	18	630	12	0.46	<5	494	0.31	43	10	14

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method / Analyte / Units / LOR	Pb-AA62 / Pb / % / 0.01
B292560		
B292561		
B292562		
B292563		
B292564		
B292565		
B292566		
B292567		
B292568		
B292569		
B292570		
B292571		
B292572		
B292573		
B292574		
B292575		
B292576		
B292577		
B292578		
B292579		
B292580		
B292581		
B292582		
B292583		
B292584		
B292585		
B292586		
B292587		
B292588		
B292589		
B292590		
B292591		
B292592		
B292593		
B292594		
B292595		
B292596		
B292597		
B292598		
B292599		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292600		7.18	0.080	<0.5	7.24	3260	1320	3.2	17	1.68	<0.5	9	79	81	2.22	0.01
B292601		0.80	0.058	<0.5	6.65	2470	1250	2.8	13	3.11	<0.5	8	117	85	2.18	0.01
B292602		0.88	0.085	<0.5	6.96	2850	1150	2.7	14	2.05	<0.5	8	85	83	1.92	0.01
B292603		3.04	0.108	<0.5	7.43	3320	1460	3.1	30	1.58	<0.5	9	120	87	2.30	<0.01
B292604		3.26	0.104	<0.5	7.43	4160	1340	3.1	16	2.12	<0.5	8	89	77	2.24	<0.01
B292605		6.88	0.116	<0.5	7.23	3130	1370	3.2	24	2.12	<0.5	7	115	92	2.31	0.01
B292606		5.74	0.147	<0.5	7.39	4110	1490	3.1	27	1.79	<0.5	9	93	110	2.47	<0.01
B292607		5.58	0.077	<0.5	7.37	2660	1410	3.1	15	1.91	<0.5	7	112	79	2.11	<0.01
B292608		6.64	0.070	<0.5	7.65	2050	1440	3.1	13	2.04	<0.5	9	74	128	2.23	0.01
B292609		<0.02	0.087													
B292610		0.10	1.470	<0.5	6.96	1250	720	5.6	<2	0.01	<0.5	5	215	39	3.71	0.06
B292611		2.54	0.099	<0.5	7.42	6970	1400	3.3	15	2.25	<0.5	13	111	69	2.65	0.01
B292612		1.08	0.141	<0.5	8.33	4060	1580	1.9	23	1.69	<0.5	8	61	184	2.63	<0.01
B292613		2.68	0.058	<0.5	7.41	2140	1320	3.1	10	2.33	<0.5	6	104	69	2.39	<0.01
B292614		4.78	0.037	<0.5	7.29	1340	1260	3.2	8	1.63	<0.5	6	73	50	2.02	0.01
B292615		6.30	0.043	<0.5	7.50	1415	1360	3.2	6	2.35	<0.5	8	108	92	2.37	0.01
B292616		1.38	<0.005	<0.5	0.10	13	20	<0.5	<2	17.95	<0.5	<1	7	5	0.09	<0.01
B292617		5.90	0.062	<0.5	7.15	1970	1420	2.9	10	2.56	<0.5	8	85	64	2.20	0.01
B292618		4.42	0.093	<0.5	7.04	2630	1430	3.3	21	2.31	<0.5	8	77	85	2.24	0.01
B292619		6.82	0.126	<0.5	6.76	2730	1150	3.2	23	2.41	<0.5	7	108	56	2.10	0.01
B292620		6.58	0.121	<0.5	7.10	2750	1150	3.3	23	2.02	<0.5	8	95	65	2.35	0.01
B292621		2.94	0.047	<0.5	7.44	1080	1290	3.0	6	2.62	<0.5	7	110	70	2.43	0.01
B292622		4.60	0.044	<0.5	6.95	1025	1290	2.9	7	2.58	<0.5	7	83	64	2.34	0.01
B292623		8.70	0.051	<0.5	7.12	927	1180	2.9	9	2.15	<0.5	5	91	40	2.09	0.01
B292624		5.32	0.117	<0.5	7.40	2010	1500	3.0	13	2.01	<0.5	8	74	49	2.06	0.01
B292625		6.76	0.137	<0.5	7.13	2050	1120	2.7	15	3.01	<0.5	6	102	49	2.06	0.01
B292626		6.82	0.158	<0.5	7.35	2070	1510	2.9	10	3.02	<0.5	6	73	51	2.18	0.01
B292627		7.62	0.229	<0.5	6.37	3350	1260	2.5	17	2.60	<0.5	9	99	63	1.98	0.01
B292628		5.72	0.214	<0.5	7.48	4830	1440	3.0	23	2.14	<0.5	10	98	46	2.61	0.01
B292629		<0.02	0.228													
B292630		0.10	3.26	<0.5	6.82	15	2070	3.0	<2	4.61	<0.5	22	140	95	4.90	<0.01
B292631		5.78	0.221	<0.5	7.71	5610	1720	2.7	23	2.16	<0.5	8	119	61	3.01	<0.01
B292632		6.26	0.152	<0.5	7.33	1930	1490	2.7	10	2.26	<0.5	9	90	69	2.57	0.01
B292633		2.00	0.385	<0.5	7.57	3560	1800	2.6	14	1.44	<0.5	8	104	58	2.88	<0.01
B292634		5.22	0.167	1.7	7.45	2810	460	2.4	6	1.26	4.5	5	85	88	3.97	0.06
B292635		1.42	0.058	<0.5	8.09	868	1820	3.3	5	1.52	<0.5	8	33	57	3.31	0.01
B292636		1.78	<0.005	<0.5	0.15	6	20	<0.5	<2	19.95	<0.5	<1	3	2	0.13	<0.01
B292637		2.06	0.106	1.5	7.20	1430	680	2.3	2	2.70	9.5	6	23	61	4.18	0.11
B292638		3.06	1.030	5.0	5.49	>10000	20	1.9	13	0.21	31.3	6	22	303	15.90	0.34
B292639		1.02	0.287	3.2	7.59	3390	180	2.8	8	0.45	4.4	7	27	135	5.94	0.09

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292600		4.50	0.80	106	2	1.60	18	570	7	0.52	<5	437	0.27	38	10	13
B292601		3.84	0.84	684	5	1.37	17	570	15	0.35	<5	435	0.28	38	20	44
B292602		3.75	0.78	533	2	1.20	17	560	12	0.33	5	371	0.27	36	20	26
B292603		4.27	0.82	111	5	1.48	18	610	10	0.62	<5	458	0.29	38	10	14
B292604		4.27	0.83	141	1	1.59	16	550	12	0.47	5	420	0.28	39	10	15
B292605		4.30	0.88	124	1	1.63	16	600	6	0.51	6	433	0.29	40	20	20
B292606		4.65	0.96	104	1	1.55	20	630	9	0.59	<5	468	0.30	41	40	12
B292607		4.26	0.87	118	1	1.57	15	560	12	0.46	<5	463	0.28	37	30	13
B292608		4.99	0.80	125	6	1.56	16	600	6	0.59	5	443	0.29	38	40	35
B292609																
B292610		2.66	0.35	87	2	0.11	19	320	18	0.01	114	92	0.21	90	<10	43
B292611		4.22	0.82	146	1	1.68	18	590	11	0.63	7	482	0.28	38	10	15
B292612		5.33	0.70	118	13	0.89	10	540	14	0.90	<5	406	0.27	33	40	10
B292613		4.10	0.94	194	2	1.58	13	570	10	0.38	<5	475	0.27	40	10	21
B292614		3.97	0.87	145	1	1.53	14	540	13	0.24	<5	456	0.26	38	10	18
B292615		3.77	0.88	190	1	1.74	15	580	4	0.39	<5	465	0.28	41	10	20
B292616		0.03	10.65	136	<1	0.01	1	460	<2	0.01	<5	106	<0.01	2	<10	6
B292617		3.49	0.89	185	2	1.67	18	580	7	0.40	<5	486	0.26	35	10	13
B292618		4.10	0.86	157	1	1.67	14	600	8	0.42	<5	485	0.30	41	10	17
B292619		3.98	0.76	186	<1	1.38	11	520	16	0.42	<5	379	0.24	37	10	26
B292620		4.04	0.91	187	1	1.50	13	540	12	0.40	5	429	0.26	43	20	24
B292621		4.03	0.96	249	2	1.37	16	610	15	0.34	<5	426	0.28	47	30	26
B292622		4.04	0.92	255	1	1.35	13	600	14	0.32	6	400	0.28	46	30	25
B292623		4.06	0.81	213	1	1.17	14	540	23	0.23	<5	401	0.26	35	20	35
B292624		4.21	0.86	203	2	0.96	17	640	17	0.28	10	396	0.30	39	20	62
B292625		3.94	0.70	268	2	0.75	17	560	30	0.43	16	312	0.26	35	20	69
B292626		4.38	0.89	278	<1	1.00	14	600	22	0.37	6	443	0.29	40	30	38
B292627		4.46	0.74	207	<1	0.85	17	520	21	0.44	11	357	0.28	35	20	39
B292628		4.03	0.86	219	1	1.56	15	580	22	0.46	7	462	0.28	43	40	42
B292629																
B292630		3.29	2.85	993	13	2.28	64	2230	17	0.30	<5	1600	0.37	162	<10	90
B292631		4.34	0.94	211	1	1.29	20	660	24	0.60	9	468	0.31	47	30	38
B292632		3.80	0.82	264	7	1.18	23	620	27	0.64	14	414	0.29	40	90	88
B292633		4.05	0.80	224	2	1.00	21	660	10	0.45	24	353	0.30	42	50	21
B292634		3.80	0.72	579	1	0.12	17	600	367	2.44	154	108	0.24	35	30	671
B292635		3.91	0.79	173	1	1.27	25	650	19	0.43	23	450	0.31	43	10	34
B292636		0.03	11.65	144	<1	0.01	3	520	2	0.01	<5	118	0.01	2	<10	11
B292637		3.34	0.97	2080	2	0.04	18	570	791	1.64	351	84	0.25	35	20	1380
B292638		2.67	0.33	215	<1	0.03	16	470	3000	>10.0	1570	12	0.18	28	10	4750
B292639		3.59	0.53	287	2	0.09	21	600	184	5.31	104	44	0.23	36	30	675

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method / Analyte / Units / LOR	Pb-AA62 / Pb / % / 0.01
B292600		
B292601		
B292602		
B292603		
B292604		
B292605		
B292606		
B292607		
B292608		
B292609		
B292610		
B292611		
B292612		
B292613		
B292614		
B292615		
B292616		
B292617		
B292618		
B292619		
B292620		
B292621		
B292622		
B292623		
B292624		
B292625		
B292626		
B292627		
B292628		
B292629		
B292630		
B292631		
B292632		
B292633		
B292634		
B292635		
B292636		
B292637		
B292638		
B292639		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292640		5.26	0.065	0.9	7.99	1195	1720	3.0	5	0.96	0.5	7	32	72	3.54	0.01
B292641		3.22	0.232	0.6	7.35	3040	1350	2.5	18	1.22	1.3	7	28	106	2.57	0.02
B292642		2.86	0.377	0.7	7.38	3850	1440	2.6	31	1.24	1.1	7	29	96	2.85	0.02
B292643		4.20	0.095	<0.5	7.52	1910	1640	2.9	9	2.43	<0.5	7	30	73	2.32	<0.01
B292644		2.14	0.265	4.8	6.93	6570	540	2.7	19	1.67	40.0	8	22	200	3.47	0.44
B292645		6.20	0.140	1.6	6.98	1100	1260	2.4	2	1.93	1.7	6	29	241	2.91	0.03
B292646		7.18	0.152	<0.5	7.25	3320	1560	2.5	19	1.71	<0.5	7	27	162	2.39	<0.01
B292647		6.04	0.103	<0.5	6.93	2970	1540	2.6	13	2.56	<0.5	6	29	91	2.30	<0.01
B292648		5.74	0.108	<0.5	7.29	3050	1460	2.6	18	2.29	<0.5	7	29	90	2.51	0.01
B292649		<0.02	0.104													
B292650		0.10	2.48	<0.5	7.69	2190	760	12.6	<2	0.01	<0.5	1	150	104	3.45	0.08
B292651		6.10	0.122	<0.5	7.43	3150	1540	2.6	14	2.01	<0.5	8	30	59	2.42	<0.01
B292652		6.22	0.041	<0.5	7.89	2070	1640	3.0	6	2.54	<0.5	8	35	63	2.60	<0.01
B292653		4.76	0.062	<0.5	6.94	1825	1400	2.5	8	2.31	<0.5	8	30	65	2.40	<0.01
B292654		5.40	0.123	<0.5	7.33	2230	1480	2.8	14	2.33	<0.5	8	32	42	2.45	0.02
B292655		1.86	0.094	<0.5	7.15	2030	1540	2.9	10	2.19	<0.5	7	54	61	2.26	0.01
B292656		5.26	<0.005	<0.5	0.12	8	10	<0.5	<2	18.85	<0.5	<1	3	6	0.11	<0.01
B292657		6.02	0.162	<0.5	6.93	2970	1410	2.6	22	2.25	<0.5	9	51	79	2.42	0.01
B292658		5.54	0.318	1.0	7.00	4600	1110	2.7	26	2.66	1.5	11	53	49	3.08	0.03
B292659		6.60	0.131	<0.5	7.06	2280	1500	2.9	8	2.15	<0.5	10	51	73	2.47	0.01
B292660		2.18	1.170	1.2	6.52	9190	290	2.2	21	1.12	0.6	8	57	99	3.99	0.03
B292661		0.66	0.529	2.2	4.47	6450	490	1.4	8	1.66	1.3	7	20	77	2.58	0.02
B292662		1.18	0.615	3.2	5.87	8300	440	1.8	12	1.54	<0.5	8	53	71	2.86	0.01
B292663		2.50	0.865	1.5	7.16	6950	340	2.2	7	2.75	1.5	8	25	64	3.00	0.02
B292664		1.08	0.780	5.3	2.03	5430	130	0.9	19	0.81	5.1	3	55	40	3.06	0.09
B292665		5.26	0.167	2.2	7.25	2590	420	2.6	8	1.00	10.6	6	25	151	3.79	0.13
B292666		5.68	0.458	1.2	7.05	7380	840	2.3	23	2.17	1.8	9	51	81	3.20	0.02
B292667		3.38	0.341	3.3	7.34	5230	520	2.5	44	2.64	3.0	8	23	79	2.67	0.05
B292668		1.24	1.350	9.9	2.31	4660	20	0.9	55	3.74	20.7	8	29	146	16.45	0.43
B292669		<0.02	1.380													
B292670		0.10	4.57	8.7	7.15	6	470	0.9	<2	2.69	1.3	17	22	123	3.99	0.01
B292671		2.14	0.207	2.3	7.24	3640	1000	2.6	20	2.10	2.4	9	43	52	2.05	0.07
B292672		6.66	0.186	0.8	7.27	3200	1250	2.7	19	2.46	<0.5	7	28	48	2.28	0.02
B292673		6.36	0.220	2.0	7.24	6060	980	2.6	19	2.81	1.9	7	51	68	2.71	0.04
B292674		6.02	0.219	<0.5	7.48	5030	1470	2.7	25	2.53	<0.5	7	30	60	2.62	0.02
B292675		6.02	0.212	3.8	7.42	4250	590	2.6	18	2.70	6.4	9	49	97	2.79	0.09
B292676		2.48	<0.005	<0.5	0.14	31	20	<0.5	<2	20.3	<0.5	<1	2	2	0.13	<0.01
B292677		3.72	0.157	1.5	7.24	4350	1100	2.9	19	2.42	11.3	8	44	100	2.88	0.18
B292678		2.00	0.114	<0.5	7.40	2480	1580	3.0	13	2.49	<0.5	9	27	58	2.40	0.01
B292679		6.40	0.240	<0.5	7.00	4030	1380	2.8	14	2.26	<0.5	9	43	78	2.16	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292640		4.28	0.83	313	2	0.68	22	680	67	0.62	58	327	0.31	40	20	106
B292641		4.54	0.66	221	1	0.53	18	590	87	0.93	45	244	0.27	36	30	207
B292642		4.47	0.70	235	2	0.53	20	610	67	1.04	28	254	0.27	37	30	215
B292643		4.19	0.72	196	<1	1.39	21	640	10	0.58	15	485	0.31	39	20	20
B292644		3.40	0.77	716	4	0.13	17	500	954	2.49	321	112	0.21	31	<10	5720
B292645		4.10	0.69	398	1	0.39	18	600	93	1.25	53	223	0.26	39	10	282
B292646		4.25	0.72	176	1	1.06	22	610	22	0.40	23	366	0.28	37	20	25
B292647		4.39	0.71	168	2	1.35	18	600	18	0.52	12	463	0.30	39	30	22
B292648		4.10	0.72	250	1	1.17	20	640	45	0.62	16	390	0.30	40	40	83
B292649																
B292650		3.25	0.39	68	2	0.09	10	330	25	0.03	160	144	0.20	108	10	16
B292651		4.10	0.87	182	1	1.41	18	620	16	0.40	9	462	0.30	39	70	29
B292652		4.25	0.92	197	1	1.73	22	660	13	0.44	7	562	0.33	43	10	24
B292653		3.64	0.79	259	5	1.26	18	600	19	0.50	9	429	0.30	39	20	52
B292654		3.83	0.84	273	1	1.41	18	630	17	0.39	12	442	0.31	40	20	46
B292655		4.08	0.81	182	1	1.48	20	610	12	0.39	7	487	0.30	38	20	20
B292656		0.03	10.90	144	<1	0.01	6	480	3	0.01	<5	104	0.01	2	<10	10
B292657		4.15	0.95	319	2	1.02	19	620	24	0.56	25	392	0.30	40	30	34
B292658		3.97	1.17	519	1	0.54	34	680	130	0.68	40	292	0.29	45	30	237
B292659		3.95	0.64	214	1	1.27	16	600	21	0.51	12	402	0.29	37	30	45
B292660		3.30	0.62	229	3	0.51	19	530	172	2.28	102	231	0.23	33	30	142
B292661		2.36	0.72	566	1	0.04	13	350	277	1.13	162	94	0.12	21	20	178
B292662		3.40	0.71	513	1	0.07	16	470	6160	1.57	2940	122	0.16	26	30	79
B292663		3.13	0.97	1495	4	0.03	22	560	208	0.56	102	96	0.24	34	10	288
B292664		0.90	0.38	446	1	0.02	8	160	835	2.32	334	31	0.06	10	10	717
B292665		3.51	0.68	867	3	0.04	17	580	341	2.16	135	51	0.23	36	20	1590
B292666		3.86	0.89	607	7	0.21	16	570	93	1.33	65	182	0.24	35	30	259
B292667		3.50	1.00	1190	5	0.08	19	570	209	0.49	114	134	0.24	35	20	517
B292668		1.05	1.12	4990	<1	0.01	15	170	>10000	>10.0	>10000	118	0.06	12	<10	3300
B292669																
B292670		2.24	1.29	923	13	1.67	14	860	26	0.69	17	393	0.37	149	<10	93
B292671		4.34	0.81	792	1	0.34	18	600	146	0.43	73	214	0.27	36	40	390
B292672		3.93	0.77	430	<1	0.78	17	600	48	0.47	25	327	0.28	36	60	70
B292673		3.96	0.83	670	<1	0.52	21	590	162	0.69	34	248	0.26	36	30	323
B292674		4.35	0.88	329	1	1.03	23	630	22	0.68	27	391	0.28	38	40	35
B292675		3.53	0.84	1680	2	0.13	20	640	303	0.78	104	152	0.27	39	30	1020
B292676		0.04	11.55	162	<1	0.01	5	490	2	0.01	<5	120	0.01	2	<10	10
B292677		3.93	0.69	675	<1	0.61	20	620	578	1.34	232	250	0.28	37	170	1800
B292678		4.16	0.68	246	2	1.50	21	620	17	0.42	21	446	0.30	38	30	26
B292679		4.62	0.59	200	1	1.11	16	520	21	0.58	16	381	0.27	34	40	25

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method Analyte Units LOR	Pb-AA62 Pb % 0.01
B292640 B292641 B292642 B292643 B292644		
B292645 B292646 B292647 B292648 B292649		
B292650 B292651 B292652 B292653 B292654		
B292655 B292656 B292657 B292658 B292659		
B292660 B292661 B292662 B292663 B292664		
B292665 B292666 B292667 B292668 B292669		2.54
B292670 B292671 B292672 B292673 B292674		
B292675 B292676 B292677 B292678 B292679		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292680		5.46	0.099	<0.5	7.26	1530	1560	2.9	10	2.03	<0.5	8	25	57	2.11	0.01
B292681		1.22	0.124	1.3	7.23	2580	900	2.7	8	3.55	6.5	7	43	68	2.74	0.06
B292682		1.22	0.173	1.4	7.25	2200	910	2.7	6	3.27	3.8	7	39	74	2.43	0.04
B292683		4.26	0.145	<0.5	7.34	3350	1550	3.1	33	2.12	<0.5	9	50	68	2.44	0.01
B292684		3.72	0.103	1.4	7.18	2290	1150	3.0	18	3.61	4.4	6	25	60	2.62	0.06
B292685		1.94	0.071	1.5	7.57	765	860	3.1	3	3.71	2.6	8	79	52	2.25	0.04
B292686		6.88	0.081	<0.5	7.83	1585	1480	3.2	17	2.55	<0.5	7	94	54	2.36	0.01
B292687		6.34	0.761	1.5	7.41	1170	660	3.0	3	3.25	15.1	8	75	72	3.09	0.21
B292688		6.78	0.140	<0.5	7.82	3030	1560	2.9	11	2.18	0.5	8	94	80	2.57	0.01
B292689		<0.02	0.127													
B292690		0.10	0.461	2.8	9.37	6	1120	1.2	<2	1.52	0.7	8	13	7210	3.33	0.03
B292691		5.54	0.023	<0.5	7.46	487	1660	3.2	<2	2.52	<0.5	7	72	48	2.19	0.01
B292692		3.06	0.040	<0.5	6.93	457	1490	2.8	2	2.21	<0.5	8	90	34	1.92	<0.01
B292693		3.48	0.030	1.8	7.87	410	640	3.2	<2	2.96	6.0	8	89	45	2.23	0.11
B292694		5.84	0.079	<0.5	7.78	1850	1380	2.9	2	2.44	0.5	8	94	46	2.37	0.02
B292695		6.70	0.073	<0.5	7.11	2560	1260	2.8	19	2.54	1.2	7	80	38	2.55	0.03
B292696		1.68	<0.005	<0.5	0.29	<5	40	<0.5	<2	19.25	<0.5	<1	9	2	0.17	<0.01
B292697		6.00	0.038	<0.5	7.62	1450	1460	3.2	2	2.95	<0.5	7	79	41	2.29	0.01
B292698		6.48	0.143	0.8	7.88	1920	1230	3.1	15	2.51	0.9	8	99	58	3.05	0.02
B292699		3.90	0.078	2.4	7.78	935	580	3.6	7	2.04	4.3	8	85	76	3.75	0.06
B292700		3.06	1.165	9.4	5.40	1915	70	2.5	30	3.37	20.6	5	84	288	8.21	0.26
B292701		2.88	0.065	<0.5	7.14	1485	1560	3.0	5	1.72	<0.5	8	77	38	2.23	<0.01
B292702		2.70	0.047	<0.5	7.27	1440	1580	3.1	4	1.58	<0.5	12	96	41	2.19	<0.01
B292703		5.46	0.055	<0.5	6.98	1935	1520	3.0	10	1.79	<0.5	6	77	45	2.21	<0.01
B292704		5.88	0.061	<0.5	7.33	1530	1360	3.1	6	1.86	<0.5	7	96	44	2.14	<0.01
B292705		5.68	0.118	<0.5	7.53	1160	1260	3.2	12	2.67	<0.5	8	88	46	2.60	<0.01
B292706		5.44	0.049	<0.5	6.91	1015	1340	3.0	4	2.26	<0.5	9	88	43	2.12	<0.01
B292707		3.38	0.022	<0.5	6.94	356	1320	3.0	<2	2.15	<0.5	13	80	50	2.13	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292680		4.08	0.69	187	1	1.51	20	580	13	0.38	<5	443	0.29	35	90	21
B292681		3.87	1.01	806	1	0.29	14	560	321	0.85	29	265	0.24	34	10	995
B292682		4.06	0.97	680	1	0.28	19	600	238	0.66	32	251	0.27	40	20	623
B292683		4.08	0.78	222	1	1.48	17	600	21	0.47	9	458	0.31	38	30	28
B292684		3.82	0.80	729	<1	0.69	17	580	463	0.70	70	350	0.26	36	20	699
B292685		4.00	0.68	797	<1	0.25	18	550	284	0.52	24	282	0.25	34	20	439
B292686		4.19	0.84	341	<1	1.59	16	600	22	0.43	11	504	0.30	43	10	30
B292687		3.48	0.80	1590	<1	0.16	18	570	424	1.67	145	169	0.26	36	10	2400
B292688		4.44	0.91	417	2	0.97	20	640	64	0.66	32	342	0.30	38	20	67
B292689																
B292690		3.71	1.17	486	4	3.50	8	1900	67	0.26	<5	702	0.35	180	10	66
B292691		4.07	0.90	298	2	1.62	20	620	14	0.30	8	491	0.30	37	20	29
B292692		4.15	0.82	351	1	1.44	19	560	15	0.27	10	423	0.28	35	40	25
B292693		3.70	0.83	1370	3	0.20	20	640	509	0.39	45	157	0.27	40	10	975
B292694		4.30	0.86	545	2	0.91	18	610	64	0.46	42	298	0.28	37	20	95
B292695		4.26	0.85	522	2	1.12	17	600	80	0.39	45	301	0.27	38	10	200
B292696		0.03	11.00	152	<1	0.04	10	560	<2	0.02	<5	116	0.01	2	<10	7
B292697		4.44	1.08	505	2	1.04	19	600	25	0.30	25	335	0.22	38	10	45
B292698		3.97	0.93	897	2	0.66	17	660	185	0.89	91	259	0.29	42	10	184
B292699		3.44	1.01	1110	2	0.17	23	650	333	1.23	64	137	0.27	41	20	669
B292700		2.30	0.80	2110	<1	0.07	12	400	>10000	8.40	6280	132	0.16	27	20	3120
B292701		4.18	1.04	464	<1	1.57	23	610	35	0.22	29	444	0.29	40	30	35
B292702		4.16	1.02	404	<1	1.62	18	620	29	0.23	17	447	0.29	41	20	34
B292703		4.26	1.02	364	1	1.47	18	600	35	0.30	17	416	0.27	38	20	28
B292704		3.99	0.98	274	<1	1.50	18	530	22	0.30	<5	467	0.28	38	30	28
B292705		3.69	0.94	540	1	1.26	20	650	51	0.62	9	397	0.28	40	10	89
B292706		3.76	0.84	271	1	1.56	19	590	28	0.29	5	439	0.27	37	20	47
B292707		3.84	0.97	283	1	1.67	18	590	21	0.22	5	445	0.27	40	20	28

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 29-JUN-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05047825

Sample Description	Method	Pb-AA62
	Analyte	Pb
	Units	%
	LOR	0.01
B292680 B292681 B292682 B292683 B292684		
B292685 B292686 B292687 B292688 B292689		
B292690 B292691 B292692 B292693 B292694		
B292695 B292696 B292697 B292698 B292699		
B292700 B292701 B292702 B292703 B292704		1.32
B292705 B292706 B292707		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da( )-JUL-2005
Account: STRGOL

CERTIFICATE VA05049843

Project: Dublin Gulch-1735

P.O. No.:

This report is for 143 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 23-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B292034		4.76	0.134			3.6	7.83	2080	730	3.4	8	0.13	9.6	6	32	104
B292035		4.98	0.052			2.8	7.31	1060	720	3.1	3	0.55	15.8	26	18	84
B292036		2.10	0.006			<0.5	0.22	28	20	<0.5	<2	20.3	<0.5	1	1	3
B292037		5.86	0.034			2.5	7.44	1350	1000	3.1	3	0.71	19.3	19	19	100
B292038		5.56	0.035			2.1	7.51	1090	1620	2.5	5	1.69	2.5	13	22	119
B292039		3.00	0.021			0.6	6.72	1180	1230	2.6	<2	2.22	2.0	14	18	81
B292040		3.54	0.056			0.8	6.97	1955	1130	3.0	4	2.32	2.4	19	25	104
B292041		2.60	0.091			2.2	6.79	3780	1370	2.4	14	2.06	1.3	15	15	103
B292042		3.02	0.060			1.5	7.23	2150	1480	2.6	6	2.10	1.3	13	19	105
B292043		3.36	0.099			1.8	7.10	5040	1340	2.6	12	2.19	2.8	25	21	151
B292044		2.42	0.702			12.7	3.72	4890	370	1.6	46	0.16	1.0	20	16	240
B292045		3.36	0.022			1.0	7.44	490	1070	2.7	3	3.00	1.7	8	41	59
B292046		3.22	0.863			3.0	7.44	1260	1560	2.8	80	1.96	1.5	18	20	95
B292047		1.66	0.103			3.0	7.34	2300	730	3.3	7	1.72	6.9	8	108	126
B292048		5.34	0.059			1.7	7.46	1685	650	3.0	8	3.23	7.1	6	100	96
B292049		0.04	0.056													
B292050		0.10	4.70			9.0	7.33	11	470	0.9	<2	2.80	1.0	19	19	123
B292051		2.28	0.035			1.1	6.80	862	620	3.0	7	2.87	0.7	7	97	51
B292052		4.46	0.028			0.7	7.58	947	1710	3.2	<2	1.94	<0.5	14	116	60
B292053		3.66	0.118			0.5	7.39	1980	1680	2.9	19	1.60	0.6	16	93	69
B292054		4.50	0.050			<0.5	7.91	1140	1690	3.1	4	1.72	<0.5	14	110	50
B292055		5.46	0.212			2.0	6.60	2450	980	3.0	32	2.66	1.2	12	110	70
B292056		1.84	<0.005			<0.5	0.14	10	20	<0.5	<2	21.5	<0.5	1	13	18
B292057		3.04	0.043			1.7	6.52	2170	760	2.7	5	2.46	1.7	7	139	68
B292058		1.92	0.025			1.4	7.65	1300	1350	2.6	2	1.51	1.0	11	116	80
B292059		3.60	0.007			<0.5	6.32	512	1130	2.8	<2	3.00	1.2	10	98	32
B292060		5.96	0.120			2.1	7.43	1555	1180	2.9	9	2.39	1.4	11	117	67
B292061		1.26	0.040			1.8	7.02	1185	1230	2.6	4	2.39	2.2	11	98	78
B292062		1.04	0.034			0.9	6.81	921	1260	2.5	<2	2.25	2.4	10	98	82
B292063		2.96	0.057			0.8	6.73	1335	1200	2.7	3	2.48	1.3	11	105	46
B292064		2.42	0.013			<0.5	7.37	543	1660	3.0	<2	2.12	<0.5	10	122	44
B292065		3.14	0.023			<0.5	8.37	410	1840	3.2	<2	2.42	<0.5	12	87	73
B292066		4.92	0.015			<0.5	7.31	370	1630	2.8	<2	2.26	<0.5	11	73	32
B292067		4.60	0.180			<0.5	7.20	4120	1670	3.0	14	1.82	<0.5	13	92	60
B292068		1.26	0.028			<0.5	7.28	977	1700	3.2	<2	1.59	1.0	12	101	52
B292069		0.04	0.029													
B292070		0.10	1.435			<0.5	6.89	1370	700	6.0	<2	0.01	<0.5	6	220	40
B292071		5.32	0.097			<0.5	7.84	1570	1630	3.1	7	1.72	0.6	13	112	50
B292072		2.56	0.098			<0.5	7.65	399	1580	3.1	<2	2.44	<0.5	9	89	22
B292073		4.70	0.057			<0.5	7.53	267	1670	3.1	4	2.22	<0.5	10	110	39

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B292034		2.80	0.26	3.58	0.40	110	15	0.05	11	520	848	0.08	156	48	0.24	44
B292035		2.71	0.15	3.49	0.41	1640	6	0.03	28	550	392	0.18	44	20	0.23	33
B292036		0.15	0.01	0.08	11.50	160	<1	0.01	<1	520	20	0.02	<5	107	<0.01	2
B292037		2.90	0.15	3.96	0.43	1225	6	0.05	23	610	356	0.18	32	53	0.24	34
B292038		2.72	0.05	4.84	0.49	682	6	0.33	18	600	217	0.26	40	160	0.24	33
B292039		2.54	0.02	4.36	0.37	719	7	0.42	16	550	105	0.20	43	126	0.21	31
B292040		2.77	0.04	4.25	0.42	799	8	0.28	19	640	173	0.26	60	121	0.25	36
B292041		2.25	0.04	4.22	0.40	762	7	0.14	14	520	158	0.22	48	149	0.23	30
B292042		2.33	0.03	4.53	0.44	765	6	0.20	19	570	128	0.16	37	157	0.26	34
B292043		2.88	0.08	4.51	0.52	1045	4	0.16	17	640	170	0.34	59	164	0.27	36
B292044		2.98	0.05	1.80	0.20	181	6	0.03	6	220	461	0.26	208	203	0.13	18
B292045		2.33	0.06	4.12	0.61	1070	5	0.09	8	580	210	0.10	81	152	0.27	35
B292046		2.62	0.06	4.57	0.42	753	7	0.22	22	600	336	0.19	117	156	0.26	34
B292047		2.89	0.28	3.69	0.38	1215	69	0.04	10	630	1845	0.11	499	56	0.27	37
B292048		2.64	0.21	3.57	0.85	1630	4	0.03	8	610	726	0.15	225	123	0.27	35
B292049																
B292050		4.05	0.01	2.25	1.30	961	14	1.63	13	860	22	0.68	<5	404	0.36	148
B292051		2.39	0.03	3.85	0.39	915	6	0.09	10	620	96	0.06	41	82	0.28	41
B292052		2.55	0.02	4.25	0.58	296	4	1.22	21	620	35	0.16	25	346	0.29	37
B292053		2.71	0.02	4.22	0.66	259	4	1.05	23	620	29	0.08	33	314	0.29	37
B292054		2.64	0.02	4.06	0.59	315	4	1.10	19	650	30	0.06	39	301	0.30	39
B292055		2.47	0.04	4.07	0.30	754	7	0.07	20	600	172	0.10	61	85	0.28	39
B292056		0.14	<0.01	0.04	12.30	157	1	0.01	9	580	4	0.02	<5	118	<0.01	1
B292057		2.15	0.05	3.94	0.30	661	6	0.08	15	590	132	0.09	55	68	0.27	37
B292058		1.90	0.03	4.47	0.25	431	3	0.66	19	660	76	0.06	55	161	0.29	38
B292059		1.85	0.02	4.34	0.25	776	2	0.17	21	540	47	0.02	32	117	0.29	38
B292060		2.57	0.09	4.06	0.45	681	4	0.25	20	610	350	0.06	67	150	0.27	36
B292061		2.37	0.09	4.28	0.35	756	5	0.52	15	620	214	0.08	65	160	0.27	37
B292062		2.49	0.07	4.20	0.37	726	4	0.55	17	600	139	0.09	55	170	0.26	35
B292063		2.03	0.02	4.05	0.34	505	4	0.47	12	570	85	0.15	38	184	0.27	35
B292064		2.53	0.01	4.04	0.71	304	3	1.18	21	610	27	0.02	26	327	0.30	37
B292065		2.70	0.01	4.13	0.81	265	3	1.73	21	740	25	0.14	15	479	0.31	38
B292066		2.36	0.01	3.69	0.67	262	2	1.58	21	650	19	0.09	12	416	0.28	35
B292067		2.57	0.02	3.99	0.67	221	3	1.23	23	630	21	0.21	22	338	0.30	38
B292068		2.17	0.02	3.84	0.41	239	1	0.83	22	640	63	0.02	21	218	0.31	39
B292069																
B292070		3.76	0.06	2.77	0.35	90	1	0.11	18	320	20	0.01	112	92	0.22	95
B292071		2.87	0.01	3.97	0.67	287	<1	1.10	21	660	23	0.05	25	291	0.31	39
B292072		2.35	0.02	3.75	0.64	320	<1	1.43	19	650	16	0.05	18	372	0.30	38
B292073		2.47	0.02	3.70	0.74	279	<1	1.52	18	630	11	0.13	7	404	0.32	40

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method Analyte Units LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B292034		20	912
B292035		30	2440
B292036		<10	24
B292037		20	2630
B292038		20	567
B292039		20	474
B292040		30	576
B292041		20	337
B292042		20	360
B292043		30	516
B292044		20	241
B292045		30	248
B292046		30	579
B292047		40	645
B292048		30	481
B292049			
B292050		<10	99
B292051		20	164
B292052		20	168
B292053		50	204
B292054		20	186
B292055		30	324
B292056		<10	10
B292057		30	220
B292058		30	326
B292059		20	291
B292060		40	467
B292061		30	343
B292062		30	397
B292063		80	233
B292064		20	140
B292065		190	81
B292066		30	70
B292067		40	77
B292068		20	238
B292069			
B292070		10	47
B292071		20	137
B292072		10	78
B292073		20	41

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B292074		5.68	0.073			<0.5	6.89	737	1360	2.8	2	2.05	<0.5	10	88	64
B292075		5.82	0.061			<0.5	7.87	1425	1690	3.3	5	2.25	<0.5	11	126	51
B292076		1.56	<0.005			<0.5	0.14	<5	20	<0.5	<2	19.15	<0.5	1	6	2
B292077		2.94	0.064			<0.5	7.52	573	1700	3.1	9	2.09	<0.5	11	110	69
B292078		1.84	0.068			<0.5	7.39	682	1680	3.0	6	2.23	<0.5	10	102	30
B292079		3.92	0.021			<0.5	7.50	558	1580	3.0	2	2.10	<0.5	11	124	32
B292080		5.22	0.177			1.4	8.09	1030	1240	3.0	11	1.56	2.1	9	105	96
B292081		3.02	0.193			0.7	7.58	1760	1630	2.9	7	1.98	2.4	11	120	87
B292082		2.38	0.191			1.1	7.78	2020	1600	2.9	4	1.79	2.3	11	93	86
B292083		2.18	0.046			<0.5	7.63	739	1700	2.9	3	2.01	1.4	12	119	64
B292084		5.66	0.162			0.6	7.37	736	1530	3.0	6	2.18	0.7	10	48	62
B292085		3.94	0.132			1.2	8.36	2140	1360	2.7	18	2.96	1.3	9	61	151
B292086		1.44	0.476			2.6	7.54	1465	780	3.0	58	2.86	2.7	8	50	82
B292087		5.32	0.190			0.9	6.83	878	1100	2.6	24	1.78	1.0	15	58	127
B292088		3.22	0.218			<0.5	6.86	1285	1150	2.6	18	2.39	<0.5	18	45	110
B292089		0.04	0.226													
B292090		0.10	0.771			2.3	7.57	10	440	0.7	<2	1.86	1.0	25	96	2010
B292091		3.50	1.350			<0.5	7.16	390	1400	2.9	180	1.38	<0.5	17	64	83
B292092		5.78	0.088			<0.5	7.14	514	1610	2.8	9	1.66	<0.5	12	42	66
B292093		6.64	0.143			<0.5	7.10	165	1500	2.8	13	1.82	<0.5	10	57	59
B292094		6.64	0.058			0.8	7.03	194	1470	2.8	10	2.22	<0.5	11	41	52
B292095		4.12	0.203			0.7	7.56	107	1540	3.2	25	1.94	<0.5	10	52	41
B292096		2.36	<0.005			<0.5	0.17	<5	20	<0.5	<2	19.65	<0.5	1	1	3
B292097		6.84	0.069			<0.5	7.39	148	1460	2.7	4	2.01	<0.5	10	61	53
B292098		2.90	0.047	0.044		<0.5	7.53	122	1500	2.8	5	2.12	<0.5	12	57	83
B292099		2.78	0.036	0.054		<0.5	7.66	82	1500	3.0	9	2.22	<0.5	11	51	59
B292100		6.78	0.299	0.056	0.076	<0.5	8.06	181	1570	2.9	11	2.32	<0.5	13	68	83
B292101		3.20	0.222			<0.5	7.87	234	1560	2.9	18	2.23	<0.5	12	52	63
B292102		2.88	0.198			<0.5	8.07	121	1580	3.0	31	2.26	<0.5	9	59	47
B292103		3.82	0.014			<0.5	7.69	29	1490	2.8	<2	2.33	<0.5	7	39	37
B292104		2.42	0.039			<0.5	8.02	84	1500	2.9	4	2.38	<0.5	9	52	42
B292105		4.70	0.044			<0.5	7.62	131	1480	2.9	4	1.85	<0.5	7	40	47
B292106		6.16	0.225			<0.5	7.10	367	1400	2.8	19	1.73	<0.5	17	59	75
B292107		3.50	0.478			<0.5	7.29	305	1530	2.9	32	1.96	<0.5	16	49	75
B292108		1.86	0.154			0.5	7.46	654	570	2.9	4	1.48	0.6	16	62	96
B292109		0.04	0.171													
B292110		0.10	3.07			<0.5	7.99	2170	760	13.2	<2	0.01	<0.5	2	156	108
B292111		4.94	2.60	0.800	1.050	<0.5	7.53	580	1540	3.0	92	1.84	<0.5	18	33	80
B292112		4.24	0.438			<0.5	7.24	594	1570	2.9	33	2.01	<0.5	18	52	78
B292113		4.88	0.152			<0.5	7.27	455	1570	3.0	15	2.12	<0.5	13	49	69

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B292074		2.08	0.02	3.82	0.50	241	2	1.31	19	580	15	0.17	10	297	0.29	36
B292075		2.60	0.01	3.84	0.86	252	<1	1.62	19	640	16	0.20	<5	453	0.33	41
B292076		0.11	<0.01	0.04	11.30	155	<1	0.01	<1	490	<2	0.01	<5	110	<0.01	2
B292077		2.58	0.01	3.84	0.85	236	1	1.55	21	650	15	0.28	<5	428	0.31	40
B292078		2.54	0.01	3.59	0.82	302	<1	1.45	20	670	16	0.08	7	408	0.32	39
B292079		2.23	0.01	3.85	0.60	260	<1	1.58	21	630	19	0.08	20	365	0.31	38
B292080		2.44	0.09	3.84	0.44	263	2	0.79	22	670	311	0.11	79	205	0.31	41
B292081		2.74	0.05	4.15	0.61	336	<1	0.88	19	660	166	0.20	40	268	0.31	40
B292082		2.86	0.05	4.02	0.62	310	3	0.87	21	640	138	0.32	38	264	0.30	39
B292083		2.53	0.04	4.06	0.58	364	<1	1.01	23	670	48	0.08	26	279	0.31	40
B292084		2.56	0.01	3.93	0.65	318	<1	1.24	22	580	21	0.09	18	328	0.30	38
B292085		2.69	0.04	3.93	0.66	456	3	0.83	13	660	144	0.64	35	277	0.28	38
B292086		2.37	0.12	3.42	0.55	524	3	0.27	8	590	423	0.20	64	204	0.27	35
B292087		2.40	0.04	3.42	0.67	284	1	0.71	19	550	124	0.21	25	214	0.27	33
B292088		2.66	0.04	3.42	0.73	309	3	0.91	17	580	21	0.16	28	281	0.28	35
B292089																
B292090		5.05	0.04	1.74	1.32	427	1	3.16	48	670	8	0.63	<5	209	0.30	93
B292091		2.53	0.02	3.86	0.82	226	4	1.10	19	610	20	0.03	22	266	0.30	37
B292092		2.39	0.01	3.69	0.85	244	5	1.29	15	600	23	0.06	10	357	0.29	36
B292093		2.45	0.01	3.55	0.92	269	1	1.13	17	610	18	0.04	6	305	0.28	35
B292094		2.47	0.02	3.77	0.83	335	6	1.10	20	620	59	0.18	12	297	0.29	37
B292095		2.45	0.01	3.78	0.82	280	5	1.48	19	630	58	0.05	12	372	0.30	37
B292096		0.13	<0.01	0.05	11.65	166	<1	0.02	<1	530	3	0.01	<5	115	<0.01	2
B292097		2.27	0.01	3.37	0.85	267	5	1.19	20	560	26	0.04	<5	343	0.28	34
B292098		2.24	0.01	3.74	0.80	224	3	1.19	20	580	20	0.16	<5	346	0.28	34
B292099		2.42	0.01	3.35	0.80	221	1	1.58	24	590	26	0.23	<5	447	0.30	37
B292100		2.53	0.01	3.73	0.79	225	3	1.59	29	620	23	0.34	<5	461	0.30	36
B292101		2.42	0.01	3.71	0.74	225	2	1.57	23	600	23	0.27	<5	428	0.29	35
B292102		2.40	0.01	3.66	0.77	223	2	1.64	26	600	22	0.22	<5	450	0.30	37
B292103		2.27	0.01	3.61	0.79	236	2	1.46	23	570	19	0.15	<5	406	0.29	35
B292104		2.37	0.01	3.67	0.81	261	2	1.26	22	590	19	0.16	<5	348	0.31	37
B292105		2.36	0.04	3.49	0.81	249	2	1.37	20	600	21	0.04	<5	367	0.29	34
B292106		2.27	0.02	3.67	0.67	188	6	1.37	24	530	18	0.28	<5	367	0.27	33
B292107		2.46	0.03	4.13	0.78	198	7	1.58	22	600	20	0.18	<5	441	0.31	37
B292108		3.93	0.03	3.67	0.68	148	3	1.25	20	560	31	2.21	17	296	0.26	35
B292109																
B292110		3.63	0.11	3.36	0.40	72	3	0.10	8	340	33	0.01	161	155	0.22	108
B292111		2.55	0.01	4.08	0.76	202	7	1.56	20	610	23	0.20	<5	420	0.31	37
B292112		2.44	0.01	4.13	0.71	178	3	1.53	20	570	16	0.24	<5	424	0.29	36
B292113		2.50	0.01	3.97	0.77	199	2	1.59	18	620	22	0.17	<5	446	0.32	39

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method Analyte Units LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B292074		20	30
B292075		60	34
B292076		<10	8
B292077		20	33
B292078		10	55
B292079		10	67
B292080		30	372
B292081		20	447
B292082		30	424
B292083		30	251
B292084		40	114
B292085		40	165
B292086		60	379
B292087		40	226
B292088		50	77
B292089			
B292090		<10	202
B292091		50	41
B292092		20	64
B292093		30	45
B292094		40	114
B292095		20	59
B292096		10	9
B292097		20	48
B292098		40	32
B292099		<10	34
B292100		10	34
B292101		<10	35
B292102		<10	33
B292103		20	32
B292104		20	38
B292105		20	39
B292106		10	31
B292107		20	34
B292108		30	54
B292109			
B292110		20	18
B292111		40	35
B292112		40	27
B292113		30	32

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B292114		4.66	0.144			0.6	7.44	345	1520	2.9	10	2.04	<0.5	11	52	84
B292115		5.96	0.324			<0.5	7.30	359	1520	3.1	5	2.21	<0.5	13	30	60
B292116		2.52	<0.005			<0.5	0.13	<5	20	<0.5	<2	19.95	<0.5	2	3	2
B292117		5.94	0.092			<0.5	7.87	594	1530	3.1	10	2.23	<0.5	11	51	49
B292118		2.36	0.116			<0.5	7.97	396	1650	2.9	17	2.19	<0.5	14	31	76
B292119		4.42	0.109			<0.5	7.27	401	1400	2.8	37	2.16	<0.5	12	49	87
B292120		7.24	0.069			<0.5	7.36	288	1440	3.0	7	2.08	<0.5	11	30	44
B292121		3.26	0.152			<0.5	7.95	355	1520	3.2	7	2.21	<0.5	13	53	46
B292122		2.96	0.094			<0.5	7.50	374	1480	3.0	10	2.17	<0.5	13	35	51
B292123		5.98	0.156			<0.5	7.36	485	1580	3.1	14	3.74	<0.5	10	45	48
B292124		6.50	0.134			<0.5	7.73	363	1590	2.9	10	2.37	<0.5	9	29	39
B292125		5.54	0.156			0.8	7.72	1250	1320	2.9	14	2.28	<0.5	13	45	71
B292126		7.10	0.095			<0.5	7.81	311	1490	3.2	7	2.11	<0.5	8	30	47
B292127		6.38	0.024			<0.5	7.67	254	1420	3.0	2	2.21	<0.5	6	44	63
B292128		6.34	0.017			<0.5	7.83	101	1500	3.0	2	2.34	<0.5	9	37	40
B292129		0.04	0.018													
B292130		0.10	4.15			9.4	8.18	19	490	0.9	<2	2.84	1.3	19	32	124
B292131		5.24	0.070			<0.5	8.04	157	1640	3.1	10	2.79	<0.5	9	52	46
B292132		7.02	0.028			<0.5	7.46	173	1560	3.0	4	2.23	<0.5	8	53	41
B292133		6.26	0.009			<0.5	8.14	85	1640	3.2	<2	2.75	<0.5	9	34	17
B292134		5.70	0.038			<0.5	8.03	536	1690	3.2	6	2.42	<0.5	9	53	55
B292135		6.22	0.012			<0.5	9.40	128	1730	3.5	4	2.72	<0.5	8	31	41
B292136		1.90	<0.005			<0.5	0.12	<5	20	<0.5	<2	19.20	<0.5	<1	2	2
B292137		5.98	0.046			<0.5	9.46	765	1470	3.4	19	2.93	<0.5	7	36	70
B292138		5.62	0.060			<0.5	8.39	379	1410	3.4	12	3.16	<0.5	8	55	72
B292139		5.86	0.011			<0.5	8.92	128	1360	3.2	3	2.54	<0.5	8	37	43
B292140		6.14	0.057			<0.5	8.93	204	1400	3.0	8	2.58	<0.5	10	53	84
B292141		2.56	0.012			<0.5	9.25	91	1460	3.3	3	2.96	<0.5	9	41	19
B292142		2.60	0.025			<0.5	8.69	312	1440	3.2	3	2.94	<0.5	9	57	26
B292143		6.54	0.066			<0.5	8.86	176	1380	3.2	8	3.05	<0.5	7	35	44
B292144		6.06	0.006			<0.5	8.70	46	1420	3.3	4	2.75	<0.5	6	49	19
B292145		6.08	0.018			<0.5	8.13	148	1360	3.2	2	2.57	<0.5	8	32	52
B292146		5.92	0.088			<0.5	8.57	544	1600	3.5	8	2.87	<0.5	9	56	73
B292147		6.24	0.040			<0.5	8.97	254	1480	3.3	19	2.72	<0.5	9	35	50
B292148		3.58	0.020			<0.5	8.69	178	1600	3.4	4	2.78	<0.5	8	52	71
B292149		0.04	0.021													
B292150		0.10	0.082			<0.5	7.01	112	620	2.7	3	0.56	<0.5	60	1245	420
B292151		2.48	0.093			<0.5	8.71	216	1350	3.0	9	2.41	<0.5	11	33	168
B292152		6.42	0.012			<0.5	8.82	144	1550	3.2	3	2.55	<0.5	8	51	43
B292153		6.06	0.013			<0.5	8.00	58	1400	3.2	4	2.62	<0.5	7	28	50

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B292114		2.44	0.01	3.78	0.75	222	2	1.44	21	580	20	0.10	<5	382	0.30	36
B292115		2.40	0.01	3.73	0.76	226	2	1.67	24	610	15	0.20	<5	490	0.32	38
B292116		0.11	<0.01	0.04	11.50	159	<1	0.01	<1	520	<2	<0.01	<5	112	<0.01	2
B292117		2.45	0.01	3.84	0.82	217	2	1.64	18	610	16	0.18	<5	474	0.31	38
B292118		2.78	0.01	4.12	0.85	211	1	1.67	17	650	18	0.46	<5	472	0.31	37
B292119		2.45	0.02	3.82	0.80	218	3	1.49	18	540	22	0.31	5	431	0.29	35
B292120		2.28	0.02	3.63	0.80	230	2	1.50	20	540	22	0.19	<5	433	0.28	34
B292121		2.65	0.03	3.70	0.90	256	3	1.64	21	620	25	0.16	<5	465	0.32	40
B292122		2.50	0.01	3.70	0.82	242	3	1.58	19	590	20	0.21	<5	451	0.30	37
B292123		2.50	0.01	3.76	0.86	306	3	1.55	23	610	19	0.17	<5	503	0.31	37
B292124		2.44	0.01	3.49	0.86	256	1	1.59	24	610	19	0.15	<5	461	0.31	37
B292125		2.62	0.02	3.47	0.86	307	2	1.05	22	590	169	0.53	28	357	0.29	38
B292126		2.30	0.01	3.74	0.96	272	6	1.04	20	620	33	0.34	10	471	0.29	35
B292127		2.31	0.01	3.63	0.85	229	4	1.68	18	630	22	0.27	<5	500	0.29	36
B292128		2.40	0.01	3.47	0.87	277	3	1.73	20	590	27	0.22	<5	506	0.29	37
B292129																
B292130		4.22	0.01	2.22	1.36	973	13	1.64	18	940	26	0.71	<5	411	0.38	148
B292131		2.52	0.01	3.49	0.98	327	46	1.78	25	640	28	0.19	<5	515	0.32	39
B292132		2.43	0.01	3.25	0.92	277	2	1.61	22	600	25	0.19	<5	469	0.31	39
B292133		2.58	0.01	3.36	1.03	332	2	1.81	23	710	24	0.11	<5	527	0.34	41
B292134		2.49	0.01	3.60	0.98	261	2	1.78	25	670	22	0.23	<5	516	0.33	40
B292135		2.60	0.04	3.59	1.02	280	1	1.97	21	710	23	0.24	<5	615	0.35	41
B292136		0.10	<0.01	0.03	11.15	159	<1	0.01	3	560	2	0.01	<5	110	0.01	2
B292137		2.73	0.02	3.94	1.18	303	4	1.84	19	730	20	0.33	<5	585	0.33	46
B292138		2.66	0.01	3.96	1.06	319	8	1.83	17	680	17	0.29	<5	585	0.33	46
B292139		2.68	0.01	3.80	1.12	283	50	1.82	18	690	19	0.19	<5	532	0.32	45
B292140		2.80	0.01	3.91	1.12	309	2	1.68	18	680	19	0.32	<5	520	0.31	43
B292141		2.82	0.01	3.47	1.20	374	1	1.90	18	750	22	0.14	<5	577	0.34	48
B292142		2.70	0.01	3.43	1.11	356	2	1.85	17	710	22	0.17	<5	579	0.34	47
B292143		2.68	0.01	3.52	1.18	362	1	1.81	20	710	19	0.21	<5	543	0.32	46
B292144		2.56	0.01	3.59	1.06	339	2	1.92	15	650	22	0.12	<5	540	0.32	45
B292145		2.45	0.01	3.64	0.98	295	2	1.82	15	620	20	0.21	<5	517	0.32	42
B292146		2.66	<0.01	3.97	0.99	272	3	1.91	17	700	19	0.36	<5	578	0.35	45
B292147		2.67	0.01	3.80	1.06	319	2	1.89	15	690	29	0.23	<5	562	0.33	45
B292148		2.62	0.01	4.11	0.98	260	2	1.88	18	680	20	0.35	<5	551	0.35	43
B292149																
B292150		8.74	0.04	2.32	0.61	403	10	0.13	497	370	159	0.02	12	54	0.23	94
B292151		2.83	0.01	4.45	0.88	222	3	1.44	20	640	54	0.81	9	373	0.33	41
B292152		2.46	<0.01	3.93	0.93	270	2	1.83	19	660	23	0.23	<5	523	0.32	41
B292153		2.46	<0.01	3.54	0.94	258	3	1.70	15	620	22	0.25	<5	490	0.31	40

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B292114		30	37
B292115		20	35
B292116		<10	7
B292117		20	35
B292118		30	35
B292119		30	36
B292120		30	36
B292121		30	45
B292122		20	40
B292123		20	39
B292124		10	37
B292125		30	69
B292126		30	58
B292127		20	27
B292128		20	44
B292129			
B292130		10	97
B292131		40	52
B292132		20	52
B292133		30	43
B292134		20	32
B292135		10	29
B292136		<10	7
B292137		10	26
B292138		10	26
B292139		10	26
B292140		10	25
B292141		10	35
B292142		10	33
B292143		10	31
B292144		10	34
B292145		10	32
B292146		<10	25
B292147		<10	40
B292148		10	23
B292149			
B292150		30	615
B292151		60	59
B292152		10	28
B292153		10	25

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B292154		6.30	0.162			<0.5	7.50	58	1420	3.0	11	2.34	<0.5	7	46	75
B292155		6.00	0.043			<0.5	8.33	87	1410	3.6	7	2.45	<0.5	8	55	39
B292156		1.62	<0.005			<0.5	0.12	<5	20	<0.5	<2	19.75	<0.5	<1	2	3
B292157		5.18	0.108			<0.5	8.54	198	1580	3.2	23	2.39	<0.5	9	52	85
B292158		2.78	0.022			<0.5	8.21	489	1440	3.4	7	2.38	<0.5	7	46	70
B292159		3.34	0.080			<0.5	7.00	182	1490	2.2	14	2.20	<0.5	10	55	141
B292160		1.92	0.028			<0.5	7.58	499	1620	3.2	5	2.47	<0.5	11	53	94
B292161		3.80	0.045			<0.5	8.15	309	1480	3.0	9	2.24	<0.5	10	70	109
B292162		3.54	0.046			<0.5	8.10	327	1560	3.1	12	2.26	<0.5	10	56	145
B292163		3.44	0.172			<0.5	7.52	512	1440	2.9	11	2.22	<0.5	12	64	80
B292164		2.84	0.099			<0.5	7.85	203	1610	2.9	14	2.11	<0.5	8	50	110
B292165		6.46	0.009			<0.5	8.20	97	1590	3.4	5	2.43	<0.5	10	69	44
B292166		2.46	0.012			<0.5	8.22	172	1400	3.0	6	2.27	<0.5	7	50	42
B292167		3.90	0.257			5.0	7.12	853	510	3.1	33	2.82	5.9	9	58	107
B292168		5.04	0.063			<0.5	7.10	214	1210	2.7	9	1.76	<0.5	9	58	63
B292169		0.04	0.059													
B292170		0.10	4.36			8.3	8.40	12	500	0.9	<2	2.82	1.3	17	20	124
B292171		2.50	0.055			<0.5	7.38	289	1300	2.5	7	2.11	<0.5	6	48	52
B292172		5.68	0.042			<0.5	6.78	215	1020	1.5	12	4.12	<0.5	8	19	33
B292173		4.04	0.013			<0.5	7.80	79	1490	3.0	4	3.18	<0.5	6	58	48
B292174		5.68	0.015			<0.5	7.69	120	1560	3.2	3	2.29	<0.5	8	38	34
B292175		Not Recvd														
B292176		Not Recvd														

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B292154		2.42	<0.01	3.83	0.84	252	3	1.56	14	580	24	0.30	<5	470	0.29	35
B292155		2.36	<0.01	3.71	0.92	269	6	1.80	17	600	28	0.16	<5	493	0.31	37
B292156		0.11	<0.01	0.03	11.40	164	<1	0.01	5	530	<2	0.01	<5	109	0.01	2
B292157		2.45	<0.01	3.85	1.00	216	4	1.75	16	640	25	0.35	<5	541	0.31	40
B292158		2.29	0.01	3.74	1.16	240	2	1.44	15	610	21	0.18	5	473	0.30	40
B292159		2.36	<0.01	4.58	0.78	202	16	1.19	15	550	17	0.48	<5	437	0.25	30
B292160		2.48	0.01	3.90	1.08	244	2	1.53	14	640	17	0.30	<5	504	0.31	41
B292161		2.53	0.01	4.00	1.12	233	1	1.56	16	630	23	0.37	<5	485	0.31	41
B292162		2.68	0.01	4.00	1.08	239	5	1.62	17	630	17	0.40	<5	490	0.31	42
B292163		2.44	0.01	3.73	0.97	274	5	1.47	15	600	26	0.33	5	504	0.30	40
B292164		2.50	0.01	3.95	0.95	235	4	1.39	16	600	24	0.42	<5	448	0.29	38
B292165		2.56	0.01	3.86	1.03	361	2	1.62	22	650	30	0.15	12	498	0.35	46
B292166		2.55	0.01	3.51	0.87	355	3	1.60	18	640	22	0.13	18	406	0.30	38
B292167		3.06	0.16	2.93	0.76	692	7	0.19	13	550	539	0.67	28	252	0.25	33
B292168		2.40	0.01	3.58	0.70	287	5	0.82	14	560	39	0.39	15	255	0.25	33
B292169																
B292170		4.17	<0.01	2.27	1.37	957	12	1.63	13	900	24	0.67	<5	403	0.38	144
B292171		1.57	0.01	4.13	0.57	238	3	1.11	9	450	28	0.22	6	310	0.17	22
B292172		0.70	0.01	4.78	0.20	358	<1	1.05	2	410	25	0.12	<5	667	0.04	4
B292173		2.09	0.01	4.23	0.94	317	1	1.24	16	590	22	0.13	8	502	0.26	31
B292174		2.43	0.01	3.90	0.91	260	1	1.49	19	600	22	0.13	12	448	0.31	37
B292175																
B292176																

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049843

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B292154		20	29
B292155		20	30
B292156		<10	9
B292157		20	24
B292158		20	27
B292159		80	16
B292160		40	18
B292161		30	19
B292162		30	21
B292163		30	36
B292164		20	22
B292165		20	50
B292166		20	29
B292167		40	943
B292168		30	63
B292169			
B292170		<10	93
B292171		20	25
B292172		10	2
B292173		30	22
B292174		20	27
B292175			
B292176			

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

CERTIFICATE VA05049846

Project: Dublin Gulch-1735

P.O. No.:

This report is for 210 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 24-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: Rakesh Bopp

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291824		2.24	0.020	<0.5	5.19	323	890	1.6	<2	0.66	0.7	4	206	30	1.90	0.02
B291825		5.14	0.009	<0.5	2.14	229	220	0.5	<2	0.08	0.5	1	150	11	1.08	0.01
B291826		2.54	0.026	0.5	2.66	461	210	0.7	<2	0.23	0.8	3	283	15	1.72	0.03
B291827		2.46	0.089	1.1	3.24	621	240	1.0	4	0.08	0.8	5	190	23	1.83	0.04
B291828		5.02	0.016	0.6	3.50	540	240	0.9	<2	0.14	1.5	4	232	35	1.88	0.02
B291829		0.04	0.017													
B291830		0.10	1.265	<0.5	6.75	1255	670	5.8	<2	0.01	<0.5	5	198	37	3.59	0.05
B291831		2.76	0.132	1.5	6.11	689	430	1.8	20	0.16	1.9	9	168	51	2.57	0.04
B291832		4.02	0.087	4.3	10.35	730	850	2.3	<2	0.12	1.8	2	106	44	4.94	0.46
B291833		5.04	0.013	1.2	2.84	224	240	0.6	<2	0.03	0.8	<1	85	11	1.36	0.13
B291834		4.90	0.032	1.5	10.80	638	1050	3.0	<2	0.11	1.0	5	120	36	4.78	0.07
B291835		5.00	1.020	8.4	6.48	378	590	1.5	<2	0.07	0.5	3	115	30	3.29	0.44
B291836		1.62	<0.005	<0.5	0.12	<5	10	<0.5	<2	18.55	<0.5	<1	7	2	0.10	<0.01
B291837		2.62	0.062	1.5	1.98	258	150	0.6	<2	0.07	1.4	2	138	9	1.94	0.11
B291838		1.70	0.585	3.1	5.63	1055	870	2.7	19	0.34	7.0	7	73	153	2.96	0.08
B291839		1.98	0.294	<0.5	7.38	1360	1510	2.6	6	0.79	4.2	11	78	126	3.03	0.02
B291840		3.12	0.463	0.6	7.75	1030	1640	2.7	8	0.61	<0.5	13	103	87	2.30	0.01
B291841		1.54	1.245	0.6	7.72	967	1360	2.8	22	1.32	<0.5	10	77	72	2.71	0.02
B291842		1.10	0.767	0.7	7.97	912	1390	2.9	23	1.35	<0.5	9	97	66	2.29	0.01
B291843		7.02	0.383	<0.5	7.89	1420	1360	3.1	2	1.04	<0.5	10	75	69	2.68	0.01
B291844		2.20	0.099	<0.5	8.37	265	1680	3.1	2	2.23	<0.5	9	97	60	2.48	<0.01
B291845		5.20	0.164	<0.5	7.51	591	1460	3.0	5	1.89	<0.5	8	72	53	2.18	0.01
B291846		5.06	0.546	<0.5	7.36	279	1410	2.9	10	1.82	<0.5	7	87	44	2.08	0.02
B291847		2.22	0.086	<0.5	8.08	290	1550	3.1	<2	1.85	<0.5	8	72	45	2.26	0.01
B291848		3.40	0.063	<0.5	7.93	595	1570	3.1	<2	1.91	<0.5	10	95	47	2.39	0.01
B291849		0.04	0.089													
B291850		0.10	2.68	<0.5	7.47	2030	690	14.1	<2	0.01	<0.5	<1	146	98	3.24	0.07
B291851		3.48	0.724	<0.5	7.61	701	1520	2.8	11	1.44	<0.5	14	82	85	2.40	0.01
B291852		3.28	0.180	<0.5	7.53	632	1590	3.1	2	1.42	<0.5	9	90	75	2.36	0.01
B291853		4.08	0.332	<0.5	7.96	574	1610	2.9	18	1.57	<0.5	10	76	68	2.34	0.01
B291854		3.28	0.150	<0.5	7.88	429	1530	3.2	<2	1.78	<0.5	9	91	71	2.36	0.01
B291855		4.54	0.598	<0.5	7.91	920	1600	3.0	7	1.61	<0.5	14	75	82	2.33	0.01
B291856		1.68	<0.005	<0.5	0.13	<5	20	<0.5	<2	18.40	<0.5	<1	7	2	0.10	<0.01
B291857		1.12	0.153	<0.5	7.58	580	1480	2.9	<2	1.67	<0.5	9	78	69	2.11	0.01
B291858		4.06	0.360	<0.5	7.67	504	1590	2.9	<2	1.84	<0.5	15	83	68	2.39	0.01
B291859		4.48	0.911	<0.5	7.37	1530	1390	2.8	42	1.98	<0.5	11	72	108	2.12	0.02
B291860		6.66	0.179	<0.5	7.84	375	1530	2.9	<2	1.82	<0.5	12	102	68	2.32	0.01
B291861		2.52	4.05	<0.5	7.05	888	1270	2.7	105	1.77	<0.5	13	87	96	2.07	<0.01
B291862		3.08	0.814	<0.5	7.22	863	1300	2.7	41	1.67	<0.5	12	115	95	2.09	0.01
B291863		2.80	0.870	<0.5	8.22	359	1550	3.1	19	2.27	<0.5	10	79	60	2.44	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291824		2.16	0.37	147	2	0.54	16	500	28	0.01	26	132	0.19	32	10	182
B291825		1.00	0.11	219	2	0.04	8	130	31	0.01	22	9	0.06	12	<10	134
B291826		1.12	0.12	504	4	0.01	14	110	55	0.01	46	11	0.10	18	10	228
B291827		1.38	0.16	441	5	0.02	15	170	97	0.01	67	14	0.14	24	20	279
B291828		1.30	0.15	717	5	0.02	18	110	122	0.01	71	18	0.16	29	20	258
B291829																
B291830		2.58	0.33	87	3	0.10	19	310	27	0.01	113	84	0.25	85	10	42
B291831		1.98	0.21	564	6	0.05	23	510	153	0.02	102	48	0.22	47	20	428
B291832		3.11	0.35	74	22	0.09	18	540	1235	0.09	561	58	0.32	77	20	796
B291833		0.99	0.13	27	2	0.01	5	70	165	0.02	135	10	0.09	17	10	237
B291834		3.89	0.28	59	6	0.10	18	610	320	0.39	328	125	0.39	107	60	936
B291835		2.81	0.25	36	5	0.05	9	190	701	0.30	442	47	0.23	55	20	710
B291836		0.03	11.30	159	<1	0.01	3	500	3	0.01	<5	104	<0.01	3	<10	9
B291837		0.84	0.09	40	3	0.05	4	130	182	0.28	180	72	0.06	11	<10	251
B291838		2.52	0.51	128	8	0.23	12	530	951	0.28	295	203	0.20	30	20	956
B291839		3.44	0.85	151	4	0.95	24	650	34	0.11	62	275	0.31	36	20	689
B291840		4.26	0.46	162	1	0.88	16	620	65	0.09	53	220	0.28	37	20	122
B291841		3.91	0.51	271	4	0.98	22	640	85	0.05	64	212	0.27	37	10	33
B291842		4.12	0.48	257	4	0.97	18	670	84	0.05	59	210	0.28	37	20	29
B291843		3.85	0.63	140	1	1.12	14	600	52	0.10	31	272	0.27	36	30	39
B291844		3.73	0.89	181	2	1.84	20	670	18	0.21	5	522	0.30	38	10	23
B291845		3.80	0.83	169	1	1.58	18	580	20	0.10	7	413	0.29	35	30	24
B291846		3.49	0.85	180	1	1.46	16	550	18	0.01	7	383	0.28	33	40	23
B291847		3.88	0.84	182	1	1.68	20	620	19	0.05	<5	461	0.30	36	30	27
B291848		3.76	0.91	198	<1	1.73	19	650	18	0.02	7	453	0.32	39	50	27
B291849																
B291850		3.12	0.39	65	2	0.09	8	320	29	0.02	150	140	0.27	102	20	13
B291851		3.79	0.92	161	1	1.44	19	630	19	0.02	7	367	0.31	38	50	24
B291852		3.91	0.90	170	2	1.38	20	630	21	0.02	5	364	0.31	38	50	26
B291853		3.89	0.91	189	1	1.54	15	630	15	0.01	<5	403	0.30	37	50	21
B291854		3.72	0.90	193	1	1.60	18	610	20	0.02	11	420	0.31	37	40	26
B291855		4.02	0.90	155	1	1.49	19	630	21	0.03	9	392	0.30	37	30	21
B291856		0.04	11.50	142	<1	0.01	<1	460	5	0.01	<5	106	0.01	2	10	6
B291857		3.84	0.81	132	1	1.60	18	620	19	0.06	7	422	0.29	36	50	18
B291858		3.74	0.89	195	1	1.40	19	640	25	0.04	11	382	0.30	37	20	26
B291859		4.18	0.52	184	2	1.18	15	600	96	0.12	27	303	0.29	37	20	126
B291860		3.82	0.86	156	1	1.63	19	630	19	0.09	6	436	0.30	39	30	22
B291861		3.72	0.67	138	2	1.34	19	520	23	0.13	13	350	0.25	32	20	23
B291862		3.97	0.68	136	2	1.34	18	540	20	0.12	9	345	0.26	32	20	19
B291863		4.07	0.85	202	2	1.69	15	670	31	0.06	15	434	0.33	39	20	32

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291864		5.24	0.386	0.9	8.10	670	920	3.0	3	1.25	<0.5	9	110	116	2.30	0.03
B291865		4.88	0.186	<0.5	7.72	508	1350	3.2	4	1.78	<0.5	7	65	50	2.05	0.02
B291866		6.82	0.350	<0.5	7.66	544	1450	2.9	23	1.90	<0.5	11	106	65	2.27	<0.01
B291867		2.58	0.438	<0.5	7.91	479	1510	3.0	20	1.96	<0.5	11	70	86	2.38	0.01
B291868		3.62	0.156	<0.5	7.59	435	1540	2.9	<2	1.87	<0.5	9	108	75	2.32	0.01
B291869		0.04	0.226													
B291870		0.10	2.75	<0.5	7.69	2120	690	14.3	<2	0.01	<0.5	<1	144	102	3.24	0.07
B291871		1.68	1.040	<0.5	7.32	968	1390	2.8	31	1.49	<0.5	20	78	114	2.50	0.01
B291872		6.26	0.427	<0.5	8.13	616	1520	3.1	8	2.04	<0.5	9	109	61	2.40	0.01
B291873		1.96	0.313	<0.5	7.51	1390	1250	2.8	8	2.11	<0.5	10	81	74	2.10	0.02
B291874		3.40	0.286	<0.5	7.72	557	1380	2.9	2	1.79	<0.5	13	101	69	2.17	0.03
B291875		1.44	2.84	<0.5	8.13	616	1470	3.3	8	2.00	<0.5	12	71	59	2.57	0.01
B291876		2.22	<0.005	<0.5	0.13	7	20	<0.5	<2	19.05	<0.5	<1	6	2	0.11	<0.01
B291877		5.30	0.696	<0.5	7.68	295	1550	2.9	21	2.12	<0.5	12	87	84	2.68	0.01
B291878		7.18	0.956	0.7	7.19	559	1480	2.6	35	1.97	<0.5	14	84	81	2.50	0.02
B291879		3.64	0.829	0.7	7.31	728	1490	2.6	21	2.04	<0.5	17	101	98	2.47	0.02
B291880		5.94	1.095	<0.5	6.97	680	1450	2.5	22	1.52	<0.5	19	87	90	2.42	0.01
B291881		2.46	0.401	0.6	7.19	270	1570	2.5	13	1.97	<0.5	11	99	134	2.53	0.02
B291882		2.14	0.271	<0.5	7.62	372	1590	2.8	11	1.91	<0.5	12	86	120	2.67	0.03
B291883		5.84	0.847	<0.5	7.59	295	1550	2.6	27	2.04	<0.5	13	95	66	2.55	0.03
B291884		4.12	0.296	0.6	7.31	353	1510	2.6	21	1.94	<0.5	13	77	69	2.47	0.03
B291885		5.20	0.394	<0.5	7.34	421	1460	2.7	22	2.40	<0.5	11	93	53	2.28	0.02
B291886		6.82	0.317	<0.5	7.41	218	1490	2.6	6	2.23	<0.5	8	87	51	2.42	0.02
B291887		3.22	0.283	<0.5	7.27	616	1460	2.5	8	2.76	<0.5	14	68	155	2.52	0.01
B291888		2.76	0.691	<0.5	7.87	519	1540	2.9	14	2.22	<0.5	13	64	70	2.59	0.02
B291889		0.04	0.532													
B291890		0.12	0.930	2.5	7.22	8	440	0.7	<2	1.86	0.6	23	101	2100	5.14	<0.01
B291891		3.06	0.246	<0.5	7.29	534	1530	2.9	35	1.96	<0.5	15	89	60	2.41	0.02
B291892		4.54	0.295	<0.5	7.31	251	1480	2.7	10	1.86	<0.5	11	81	71	2.37	0.03
B291893		0.68	0.324	2.0	6.42	960	1150	2.2	6	1.52	<0.5	12	130	56	2.15	0.02
B291894		4.38	0.218	<0.5	7.00	895	1400	2.6	9	1.84	<0.5	10	92	68	2.11	0.01
B291895		2.36	0.392	<0.5	7.06	950	1460	2.7	31	1.97	<0.5	11	126	69	2.25	0.01
B291896		2.34	0.045	<0.5	7.17	280	1480	2.8	3	1.66	<0.5	7	83	41	2.09	0.02
B291897		3.96	0.269	<0.5	7.74	520	1620	2.9	13	1.96	<0.5	11	126	74	2.57	0.03
B291898		5.18	0.294	<0.5	7.30	489	1430	2.5	9	2.21	<0.5	7	96	66	2.11	0.03
B291899		5.82	0.100	<0.5	7.83	333	1720	3.2	<2	2.21	<0.5	11	29	50	2.70	0.01
B291900		2.26	0.038	<0.5	8.26	167	1630	3.2	2	2.24	<0.5	9	28	27	2.64	0.01
B291901		1.92	0.201	<0.5	8.20	1075	1630	3.1	5	2.06	<0.5	11	28	51	2.58	0.01
B291902		1.96	0.092	<0.5	7.33	657	1550	3.0	4	2.05	<0.5	8	26	45	2.35	0.01
B291903		3.62	0.144	<0.5	7.85	468	1540	3.0	10	2.12	<0.5	7	25	51	2.41	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291864		3.90	0.37	163	5	0.95	19	600	135	0.14	81	177	0.29	42	30	184
B291865		4.00	0.75	163	1	1.46	16	560	21	0.03	14	352	0.27	33	20	31
B291866		3.79	0.88	170	2	1.54	19	620	22	0.14	6	419	0.29	36	40	23
B291867		3.80	0.84	175	<1	1.66	21	640	23	0.22	7	456	0.31	38	30	28
B291868		3.98	0.99	165	1	1.38	16	630	20	0.03	<5	382	0.30	37	50	21
B291869																
B291870		3.23	0.39	65	2	0.09	9	330	30	0.02	155	143	0.26	102	20	13
B291871		3.84	0.84	139	2	1.38	20	560	19	0.07	35	370	0.27	34	70	83
B291872		4.17	0.86	176	2	1.72	17	650	21	0.11	24	432	0.31	40	30	68
B291873		3.85	0.69	204	2	1.21	15	570	41	0.15	24	314	0.27	34	30	85
B291874		3.93	0.76	164	3	1.58	19	570	30	0.27	10	404	0.27	33	20	31
B291875		3.90	1.01	214	2	1.44	21	620	19	0.10	9	416	0.31	41	40	39
B291876		0.04	12.10	147	<1	0.02	<1	480	<2	0.01	<5	115	0.01	3	10	6
B291877		3.83	0.88	225	2	1.49	20	640	19	0.38	8	442	0.30	38	40	38
B291878		3.88	0.81	217	3	1.13	20	590	55	0.12	26	333	0.28	36	20	59
B291879		4.01	0.80	223	2	0.92	20	570	49	0.14	27	310	0.27	34	20	47
B291880		3.86	0.79	180	2	1.08	23	550	22	0.12	11	305	0.27	33	20	33
B291881		3.94	0.88	210	2	1.25	20	610	18	0.06	12	335	0.30	37	30	31
B291882		3.97	0.90	211	1	1.20	21	600	24	0.07	11	338	0.30	37	30	39
B291883		3.87	0.92	234	1	1.12	21	620	16	0.05	12	338	0.31	38	30	84
B291884		3.89	0.77	247	5	0.76	25	590	46	0.11	24	275	0.30	36	20	309
B291885		4.01	0.69	229	1	1.01	20	580	17	0.12	8	336	0.28	33	20	32
B291886		3.77	0.94	215	<1	0.97	17	590	13	0.05	<5	339	0.29	36	20	31
B291887		4.12	1.08	212	3	0.66	19	570	14	0.25	<5	330	0.28	37	30	27
B291888		4.01	0.99	201	1	0.95	19	610	16	0.12	<5	362	0.29	37	30	28
B291889																
B291890		1.82	1.38	437	1	3.19	50	650	17	0.60	<5	210	0.31	93	<10	202
B291891		4.03	0.85	183	2	1.52	23	610	17	0.22	<5	437	0.31	38	30	33
B291892		3.97	0.86	182	1	1.39	21	600	17	0.14	<5	395	0.30	36	20	32
B291893		3.35	0.65	161	2	1.01	20	450	32	0.14	15	311	0.24	32	40	69
B291894		4.08	0.75	139	6	1.43	20	550	17	0.26	<5	418	0.27	33	20	24
B291895		3.88	0.80	144	1	1.49	20	600	19	0.30	<5	432	0.29	36	10	23
B291896		4.16	0.71	149	1	1.37	18	570	19	0.10	<5	357	0.27	33	10	27
B291897		4.11	0.95	196	1	1.38	24	630	15	0.18	<5	408	0.31	38	20	32
B291898		4.09	0.67	227	1	1.12	16	560	23	0.22	6	356	0.25	32	20	42
B291899		3.87	0.86	234	2	1.54	24	660	18	0.15	<5	434	0.33	41	20	39
B291900		3.87	0.85	259	<1	1.59	21	640	19	0.16	<5	442	0.31	39	10	46
B291901		4.16	0.83	208	1	1.46	22	630	19	0.19	5	409	0.31	39	20	39
B291902		3.93	0.75	205	1	1.43	21	620	18	0.19	<5	393	0.29	36	20	40
B291903		3.79	0.84	204	1	1.56	21	630	19	0.19	<5	442	0.29	36	30	32

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291904		1.84	0.417	<0.5	7.15	292	1620	2.6	15	2.28	<0.5	7	25	37	2.49	0.02
B291905		5.04	0.172	<0.5	7.17	1055	1480	2.8	6	1.97	<0.5	10	27	70	2.37	0.02
B291906		5.44	0.295	1.1	7.25	920	1160	2.8	14	2.00	1.9	6	23	56	2.19	0.05
B291907		5.48	0.447	<0.5	7.80	670	1650	3.0	14	2.11	0.7	12	30	55	2.44	0.01
B291908		6.08	0.158	<0.5	7.39	655	1460	3.1	7	1.95	<0.5	11	23	45	2.19	0.01
B291909		0.04	0.182													
B291910		0.10	4.67	8.9	8.17	<5	480	0.9	<2	2.83	1.0	18	21	128	4.32	<0.01
B291911		4.46	0.271	<0.5	7.55	695	1560	3.0	21	2.29	<0.5	11	29	72	2.65	0.01
B291912		3.20	0.446	<0.5	6.89	413	1410	2.6	9	2.53	<0.5	8	23	59	1.63	0.01
B291913		2.14	0.106	<0.5	7.54	697	1580	2.9	4	1.55	<0.5	14	27	56	3.03	0.01
B291914		3.28	0.169	<0.5	7.36	415	1220	2.5	3	3.19	<0.5	7	24	58	1.43	0.01
B291915		2.48	5.85	<0.5	7.00	903	930	2.7	75	2.45	<0.5	14	22	92	2.02	0.01
B291916		2.08	<0.005	<0.5	0.11	<5	10	<0.5	<2	19.25	<0.5	<1	2	1	0.12	<0.01
B291917		4.32	0.430	<0.5	7.65	351	1310	2.8	23	1.68	<0.5	10	24	71	2.35	0.01
B291918		2.96	1.535	<0.5	7.27	362	870	2.5	56	3.19	<0.5	9	22	54	2.19	0.01
B291919		5.44	0.308	<0.5	7.84	257	1640	3.0	20	1.86	<0.5	8	24	48	2.45	0.01
B291920		2.14	0.061	<0.5	7.37	318	1460	2.9	2	2.53	<0.5	9	24	30	2.73	0.02
B291921		1.28	0.129	0.6	8.13	78	1140	2.9	<2	2.66	1.1	6	25	21	2.19	0.05
B291922		1.26	0.187	0.9	8.01	170	1120	2.9	3	2.71	1.8	7	23	35	2.24	0.07
B291923		3.22	0.297	<0.5	7.86	621	1560	3.0	4	1.76	<0.5	10	27	35	2.66	0.02
B291924		2.40	0.234	<0.5	7.80	570	1760	2.9	4	2.18	<0.5	7	44	51	2.77	0.02
B291925		5.74	0.832	2.0	7.46	1475	890	2.7	21	2.07	1.7	10	23	96	2.92	0.05
B291926		5.08	0.440	2.5	7.84	925	1410	2.5	40	1.90	<0.5	9	43	219	2.51	0.04
B291927		5.40	0.176	<0.5	7.48	451	1560	2.9	7	1.48	<0.5	9	25	44	2.68	0.01
B291928		5.62	0.020	<0.5	7.92	85	1580	2.7	<2	2.13	<0.5	6	42	14	2.39	0.01
B291929		0.04	0.026													
B291930		0.10	0.462	2.6	9.28	<5	1060	1.2	<2	1.50	<0.5	8	8	7810	3.34	0.02
B291931		5.54	1.395	0.9	7.44	85	1400	2.8	18	2.37	<0.5	7	25	25	2.53	0.02
B291932		2.26	0.268	<0.5	6.91	243	1310	2.6	11	1.68	<0.5	7	35	30	2.45	0.02
B291933		2.22	0.113	<0.5	8.06	241	1480	2.6	4	1.94	<0.5	7	44	22	2.32	0.03
B291934		5.06	1.415	0.6	7.51	150	1560	2.5	18	2.17	0.8	7	56	32	2.50	0.05
B291935		5.54	0.635	0.8	7.40	732	1350	2.8	17	1.84	<0.5	13	63	95	2.52	0.03
B291936		1.74	<0.005	<0.5	0.17	<5	20	<0.5	<2	20.2	<0.5	<1	3	1	0.12	<0.01
B291937		2.10	0.172	0.5	7.59	113	1360	3.1	3	2.36	<0.5	7	56	45	2.35	0.02
B291938		1.74	1.720	1.3	7.42	124	1520	2.7	24	3.21	<0.5	9	71	56	2.35	0.03
B291939		2.16	0.258	0.5	7.75	122	1380	2.6	4	3.29	1.1	8	72	35	2.49	0.05
B291940		2.58	0.279	0.5	7.96	151	1530	3.3	3	2.97	<0.5	10	45	36	2.67	0.03
B291941		1.96	0.466	0.9	6.94	316	1290	2.7	10	2.62	<0.5	10	65	43	2.24	0.04
B291942		1.96	1.155	<0.5	7.71	164	1310	2.8	4	2.67	<0.5	8	49	41	2.49	0.03
B291943		4.22	1.330	<0.5	7.74	176	1680	3.1	21	2.41	<0.5	9	64	77	2.75	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291904		3.80	0.92	238	<1	1.18	18	630	16	0.05	8	387	0.31	37	30	36
B291905		3.76	0.81	200	5	1.23	20	590	27	0.32	16	356	0.28	35	20	45
B291906		3.90	0.67	464	1	0.48	13	560	247	0.49	74	198	0.25	33	20	375
B291907		4.53	0.73	203	<1	1.41	23	610	39	0.24	30	429	0.29	36	10	285
B291908		4.17	0.73	176	<1	1.57	18	550	22	0.20	6	428	0.27	33	10	58
B291909																
B291910		2.37	1.40	986	11	1.66	13	900	21	0.68	<5	424	0.38	154	<10	100
B291911		3.80	0.79	219	<1	1.45	20	590	19	0.36	<5	432	0.30	38	20	36
B291912		4.24	0.45	195	2	1.27	15	570	19	0.17	11	323	0.27	34	20	30
B291913		3.62	0.82	219	1	1.04	26	600	19	0.20	<5	317	0.30	38	30	40
B291914		3.76	0.39	297	1	1.35	15	570	18	0.17	21	308	0.28	35	20	28
B291915		3.54	0.61	174	1	1.16	20	600	24	0.54	21	278	0.29	37	30	33
B291916		0.03	11.85	156	<1	0.01	3	480	2	0.01	<5	106	0.01	3	<10	7
B291917		3.95	0.57	162	1	1.27	20	620	20	0.35	21	318	0.30	38	20	35
B291918		3.45	0.76	248	2	1.49	18	600	20	0.21	29	395	0.28	36	30	31
B291919		4.22	0.61	184	1	1.25	22	620	23	0.16	10	392	0.30	37	20	37
B291920		3.85	0.77	393	<1	0.85	19	620	31	0.62	25	335	0.29	36	20	74
B291921		3.67	0.81	472	1	0.35	12	610	225	0.77	38	220	0.27	37	30	279
B291922		3.95	0.82	604	<1	0.27	19	610	566	0.74	103	215	0.28	38	30	407
B291923		4.04	0.60	240	<1	1.02	18	560	31	0.21	19	307	0.28	39	10	49
B291924		4.12	0.64	369	<1	0.83	19	620	23	0.27	26	310	0.30	40	20	40
B291925		3.39	0.80	480	2	0.57	18	550	436	0.98	151	217	0.27	35	30	397
B291926		4.27	0.76	302	3	0.56	22	600	176	0.37	73	251	0.28	35	20	120
B291927		4.21	0.66	184	5	0.65	20	620	47	0.26	15	258	0.30	37	20	83
B291928		3.82	0.65	304	1	1.19	20	650	35	0.13	18	340	0.29	36	10	64
B291929																
B291930		3.94	1.24	494	2	3.49	9	1920	9	0.24	<5	720	0.35	185	<10	57
B291931		3.69	0.76	405	<1	0.75	19	620	76	0.22	23	276	0.31	38	20	161
B291932		3.71	0.69	266	1	0.56	15	500	116	0.13	51	244	0.23	27	20	140
B291933		3.96	0.50	368	1	0.51	18	620	38	0.16	28	243	0.30	37	20	67
B291934		3.82	0.64	443	2	0.59	18	590	137	0.39	61	247	0.28	35	20	249
B291935		4.07	0.69	398	2	0.45	21	560	52	0.38	24	219	0.27	35	20	155
B291936		0.06	12.35	163	<1	0.01	3	600	5	0.01	<5	114	0.01	2	<10	10
B291937		4.26	0.82	461	1	0.41	17	610	60	0.16	24	224	0.29	36	30	170
B291938		4.60	0.85	479	1	0.75	25	630	47	0.28	32	283	0.30	47	30	84
B291939		3.95	0.75	499	1	0.63	21	600	37	0.32	21	294	0.29	40	20	314
B291940		4.00	0.91	358	3	0.86	22	640	43	0.20	19	351	0.32	40	20	73
B291941		3.84	0.70	330	1	0.90	17	570	120	0.36	29	333	0.28	34	20	127
B291942		3.99	0.76	333	1	0.86	18	560	52	0.40	20	337	0.28	35	20	89
B291943		3.79	0.90	203	1	1.71	20	700	27	0.37	6	523	0.33	42	10	30

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291944		3.22	0.342	<0.5	7.80	265	1570	3.0	5	2.34	<0.5	13	56	79	2.72	0.01
B291945		5.74	0.309	0.5	7.84	2240	1530	3.0	7	2.26	<0.5	14	61	67	2.68	0.02
B291946		6.02	1.040	0.6	7.86	91	1650	3.1	38	2.11	<0.5	7	24	44	2.45	0.03
B291947		1.54	0.033	<0.5	7.81	44	1600	2.8	<2	2.47	<0.5	9	57	32	2.62	0.01
B291948		4.58	0.202	<0.5	7.26	122	1420	2.5	9	2.37	0.6	8	22	37	2.02	0.03
B291949		0.04	0.163													
B291950		0.10	1.525	<0.5	7.06	1325	690	6.1	<2	0.01	<0.5	6	202	40	3.85	0.06
B291951		4.74	0.242	0.6	7.21	128	1400	2.8	6	2.30	<0.5	9	48	52	2.29	0.02
B291952		2.62	0.488	<0.5	7.57	52	1570	2.9	3	1.73	<0.5	8	26	45	2.58	0.01
B291953		4.34	0.396	0.8	7.22	1675	820	2.5	16	2.67	1.2	11	56	77	2.61	0.05
B291954		5.00	0.177	1.0	7.55	1115	600	2.9	5	2.42	1.6	6	50	65	2.61	0.06
B291955		3.80	1.105	1.3	7.16	522	610	2.8	13	2.64	2.2	7	24	49	2.35	0.08
B291956		1.96	<0.005	<0.5	0.11	<5	10	<0.5	<2	18.95	<0.5	<1	5	<1	0.11	<0.01
B291957		3.08	0.107	<0.5	7.29	417	1220	2.9	2	2.14	<0.5	8	31	31	2.37	0.01
B291958		1.16	1.315	0.7	3.72	1315	650	1.6	20	1.56	<0.5	14	59	67	1.92	0.02
B291959		4.04	0.238	<0.5	7.34	231	1360	3.1	5	2.19	<0.5	8	30	38	2.32	0.01
B291960		7.48	1.530	0.5	6.71	463	1190	2.6	32	2.21	<0.5	9	51	36	2.11	0.02
B291961		1.96	0.596	<0.5	7.51	505	1400	2.8	9	2.30	<0.5	13	47	54	2.84	<0.01
B291962		2.10	0.816	<0.5	7.65	238	1430	3.0	14	2.38	<0.5	11	71	54	2.84	<0.01
B291963		5.94	0.639	<0.5	7.34	144	1330	3.5	20	2.41	<0.5	14	49	65	2.89	0.01
B291964		1.90	6.34	0.9	7.48	748	1350	3.1	131	2.47	<0.5	8	66	178	2.72	0.01
B291965		4.62	1.545	<0.5	7.44	226	1240	2.9	35	2.13	<0.5	9	42	261	2.51	0.03
B291966		5.90	0.711	<0.5	7.29	82	1340	2.7	44	2.18	<0.5	7	106	44	2.33	0.02
B291967		5.94	0.285	<0.5	7.27	280	1270	3.2	10	2.20	<0.5	12	56	56	2.50	0.02
B291968		6.34	0.627	<0.5	7.29	47	1320	3.1	39	2.42	<0.5	9	71	40	2.50	0.01
B291969		0.04	0.875													
B291970		0.10	3.14	0.8	6.84	<5	1990	3.1	<2	4.56	<0.5	24	140	97	5.03	<0.01
B291971		5.80	0.388	<0.5	7.43	60	1270	2.8	21	2.65	<0.5	9	51	44	2.55	<0.01
B291972		6.46	0.364	<0.5	7.42	49	1540	2.8	6	1.90	<0.5	7	78	55	2.48	0.01
B291973		5.40	0.170	<0.5	7.22	22	1330	2.9	4	2.72	<0.5	7	64	30	2.53	0.03
B291974		6.32	0.099	<0.5	8.48	77	1400	3.2	<2	3.04	<0.5	9	71	42	2.93	0.01
B291975		5.78	0.241	<0.5	7.23	98	1430	2.8	9	2.79	<0.5	10	69	63	2.97	0.01
B291976		1.78	<0.005	<0.5	0.14	<5	20	<0.5	<2	19.35	<0.5	<1	5	1	0.12	<0.01
B291977		6.52	1.770	<0.5	7.76	167	1440	2.8	36	2.36	<0.5	9	68	70	2.88	<0.01
B291978		5.82	0.353	<0.5	8.32	68	1510	3.0	15	2.61	<0.5	9	69	67	2.94	<0.01
B291979		6.16	1.150	<0.5	7.40	50	1480	2.9	16	2.35	<0.5	9	70	52	2.67	<0.01
B291980		6.08	0.407	<0.5	7.57	32	1410	3.0	7	2.36	<0.5	10	71	75	2.63	0.01
B291981		2.82	0.853	<0.5	7.59	58	1430	2.9	5	2.41	<0.5	10	70	53	2.63	<0.01
B291982		3.18	0.083	<0.5	7.95	74	1430	3.0	5	2.52	<0.5	9	69	53	2.64	<0.01
B291983		5.78	1.170	<0.5	7.60	152	1430	2.8	17	2.20	<0.5	12	62	73	2.68	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
/01-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291944		3.74	0.90	193	<1	1.60	18	660	16	0.39	<5	502	0.31	38	30	24
B291945		4.14	0.83	240	2	1.44	19	650	57	0.49	16	461	0.31	39	10	134
B291946		4.24	0.85	226	1	1.58	16	670	82	0.18	37	495	0.32	40	10	34
B291947		3.89	0.93	325	2	1.60	22	640	29	0.11	9	533	0.33	42	20	67
B291948		4.10	0.60	279	1	0.90	18	600	55	0.36	23	302	0.29	37	10	176
B291949																
B291950		2.86	0.36	91	1	0.11	19	310	25	0.01	111	93	0.27	96	10	48
B291951		3.97	0.73	305	1	0.98	20	620	42	0.29	21	350	0.31	39	20	71
B291952		4.01	0.83	227	3	1.27	19	620	22	0.20	20	401	0.31	39	10	34
B291953		3.64	0.86	702	4	0.24	17	600	278	0.52	139	183	0.27	37	30	290
B291954		3.58	0.95	756	1	0.03	17	600	146	0.70	82	114	0.26	37	20	354
B291955		3.24	0.70	841	2	0.04	14	520	278	0.42	110	123	0.24	33	40	468
B291956		0.03	11.60	150	<1	0.01	4	470	2	0.01	<5	106	<0.01	2	<10	8
B291957		3.76	0.63	517	1	0.56	14	570	55	0.37	31	209	0.27	39	20	105
B291958		2.00	0.41	300	5	0.31	14	280	132	0.52	43	142	0.14	19	10	148
B291959		4.01	0.71	355	<1	1.06	14	570	38	0.30	18	347	0.27	38	20	71
B291960		3.62	0.66	300	1	1.11	11	480	112	0.27	44	351	0.22	31	20	45
B291961		4.51	0.94	320	4	1.40	14	630	30	0.29	6	486	0.30	54	40	53
B291962		4.27	0.96	329	5	1.54	12	650	32	0.22	6	501	0.30	53	10	56
B291963		4.47	0.99	314	1	1.62	17	600	29	0.24	5	499	0.34	56	20	56
B291964		3.80	0.91	311	15	1.48	15	600	32	0.24	<5	488	0.28	45	30	43
B291965		3.81	0.97	328	4	1.25	13	590	30	0.18	<5	441	0.27	47	30	50
B291966		3.77	0.81	273	1	1.27	15	540	28	0.17	5	439	0.25	40	30	39
B291967		3.95	0.88	256	1	1.67	15	560	29	0.20	<5	487	0.28	42	10	42
B291968		3.78	0.89	319	<1	1.57	15	580	32	0.12	<5	487	0.28	43	20	49
B291969																
B291970		3.36	2.90	1025	12	2.23	63	2240	31	0.29	<5	1610	0.39	166	<10	94
B291971		4.00	0.95	285	2	1.33	15	550	29	0.17	<5	477	0.27	41	10	41
B291972		4.17	0.98	235	1	1.37	15	600	27	0.14	<5	467	0.28	44	10	36
B291973		3.62	1.02	324	1	1.39	14	590	16	0.12	<5	511	0.29	47	20	37
B291974		3.99	1.22	336	2	1.84	14	710	17	0.20	<5	612	0.32	56	10	36
B291975		4.23	1.14	322	2	1.60	14	660	19	0.30	<5	554	0.32	55	30	35
B291976		0.04	11.95	170	<1	0.01	3	520	<2	0.01	<5	123	<0.01	2	<10	7
B291977		4.10	1.16	251	4	1.57	14	650	16	0.35	<5	506	0.30	50	40	29
B291978		4.32	1.21	280	1	1.74	16	700	21	0.30	<5	580	0.33	52	20	35
B291979		3.80	1.02	225	1	1.67	15	640	17	0.24	<5	536	0.31	45	10	30
B291980		3.60	0.98	183	1	1.62	16	620	16	0.32	<5	506	0.31	43	30	20
B291981		3.59	1.02	239	1	1.62	18	640	16	0.23	<5	519	0.31	45	10	27
B291982		3.58	1.02	236	1	1.71	18	640	15	0.25	<5	544	0.31	45	10	28
B291983		4.17	1.02	207	2	1.52	16	630	20	0.32	<5	507	0.31	44	60	24

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B291984		5.92	0.280	<0.5	8.04	83	1460	3.0	5	2.54	<0.5	9	65	52	2.76	0.01
B291985		5.98	0.237	<0.5	8.29	74	1530	2.9	7	2.38	<0.5	8	60	80	2.76	0.01
B291986		6.10	0.963	<0.5	7.64	114	1440	3.0	25	2.10	<0.5	9	61	96	2.59	0.01
B291987		6.12	0.176	<0.5	7.68	106	1450	3.1	9	2.53	<0.5	8	58	80	2.56	<0.01
B291988		5.90	0.232	<0.5	7.86	253	1360	2.9	15	2.23	<0.5	9	80	60	2.54	0.01
B291989		0.04	0.254													
B291990		0.10	0.453	2.5	9.09	<5	1040	1.2	2	1.48	<0.5	8	9	7310	3.29	0.02
B291991		5.46	1.810	<0.5	6.95	70	1360	2.8	21	2.18	<0.5	8	68	45	2.28	0.01
B291992		4.92	0.237	<0.5	7.55	64	1450	3.1	3	2.17	<0.5	8	67	48	2.29	<0.01
B291993		5.50	0.069	<0.5	7.92	79	1430	3.1	<2	2.49	<0.5	9	59	32	2.32	<0.01
B291994		6.06	0.037	<0.5	7.51	60	1530	2.9	<2	2.48	<0.5	8	58	36	2.46	<0.01
B291995		1.96	0.087	<0.5	7.61	43	1570	2.7	<2	2.15	<0.5	8	56	57	2.59	<0.01
B291996		1.58	<0.005	<0.5	0.12	<5	10	<0.5	<2	18.35	<0.5	<1	3	2	0.11	<0.01
B291997		1.62	1.130	1.5	6.78	470	950	2.5	35	3.32	1.4	12	70	70	2.54	0.03
B291998		2.78	0.044	<0.5	6.85	42	1480	2.8	<2	2.44	<0.5	8	65	20	2.50	<0.01
B291999		5.28	0.024	<0.5	7.18	34	1370	3.4	<2	2.59	<0.5	7	47	17	2.60	<0.01
B292000		6.18	0.019	<0.5	7.00	54	1330	3.3	<2	2.51	<0.5	8	41	14	2.46	<0.01
B292001		1.28	0.022	<0.5	6.86	36	1260	3.1	<2	2.89	<0.5	7	42	14	2.46	<0.01
B292002		1.28	0.020	<0.5	7.07	129	1310	3.1	<2	2.73	<0.5	9	46	17	2.55	<0.01
B292003		4.00	0.055	<0.5	7.53	85	1390	2.9	<2	2.56	<0.5	8	40	28	2.53	0.01
B292004		2.40	0.192	<0.5	6.97	622	1560	2.7	2	2.70	4.3	12	24	53	2.41	0.06
B292005		6.16	0.154	<0.5	7.75	40	1500	3.1	3	2.19	<0.5	9	30	47	2.50	<0.01
B292006		3.94	0.177	1.9	7.15	92	720	2.8	<2	3.32	4.4	5	24	52	2.49	0.07
B292007		3.72	0.366	4.2	7.65	709	760	3.0	7	2.38	5.2	12	23	82	3.32	0.09
B292008		2.62	0.060	<0.5	6.96	54	1420	2.9	2	2.17	<0.5	8	28	33	2.33	<0.01
B292009		0.04	0.059													
B292010		0.10	2.88	<0.5	7.60	2110	750	13.3	<2	0.02	<0.5	1	145	103	3.43	0.07
B292011		5.90	0.043	<0.5	7.33	147	1430	3.2	3	2.36	<0.5	7	29	34	2.31	<0.01
B292012		5.28	0.192	<0.5	7.15	72	1370	3.1	5	2.25	<0.5	7	29	33	2.37	<0.01
B292013		4.22	0.118	<0.5	7.20	193	1540	3.2	18	1.83	<0.5	8	26	41	2.20	<0.01
B292014		6.94	0.400	<0.5	7.38	101	1470	3.2	<2	2.34	<0.5	9	32	46	2.36	<0.01
B292015		5.24	0.558	<0.5	7.27	299	1390	3.0	5	2.48	<0.5	9	39	45	2.62	<0.01
B292016		1.86	<0.005	<0.5	0.13	5	20	<0.5	<2	18.40	<0.5	<1	2	2	0.11	<0.01
B292017		6.02	0.485	<0.5	7.28	314	1180	3.2	13	2.36	<0.5	12	44	82	2.81	0.01
B292018		5.22	0.399	<0.5	7.08	125	1190	2.9	4	2.78	<0.5	11	39	34	2.63	0.01
B292019		4.14	0.561	<0.5	7.12	118	1430	2.7	8	2.45	<0.5	19	53	32	2.78	<0.01
B292020		6.26	0.269	<0.5	7.21	62	1330	2.8	<2	2.44	<0.5	10	48	39	2.65	0.01
B292021		3.44	0.276	<0.5	7.92	178	1480	2.7	3	2.64	<0.5	10	52	31	2.86	<0.01
B292022		2.96	0.255	<0.5	7.54	194	1530	2.8	5	2.66	<0.5	10	50	38	2.91	<0.01
B292023		6.00	0.109	<0.5	7.65	38	1430	2.9	<2	2.58	<0.5	10	48	29	2.77	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B291984		4.06	1.11	264	2	1.62	17	640	20	0.23	<5	539	0.32	45	40	33
B291985		3.93	1.07	214	2	1.68	17	650	21	0.34	<5	545	0.31	42	20	24
B291986		3.95	0.94	152	1	1.59	18	610	18	0.41	<5	497	0.30	41	20	18
B291987		3.90	0.98	208	2	1.60	19	660	21	0.37	<5	517	0.33	44	30	30
B291988		3.92	0.98	216	1	1.58	14	620	25	0.27	<5	502	0.30	43	30	35
B291989																
B291990		3.69	1.20	485	2	3.34	9	1900	11	0.24	<5	697	0.34	174	<10	53
B291991		3.55	0.88	251	1	1.67	15	600	21	0.19	6	455	0.28	38	20	34
B291992		3.99	0.85	242	1	1.62	17	600	23	0.22	<5	474	0.29	39	10	35
B291993		3.66	0.85	276	<1	1.78	17	610	24	0.18	<5	501	0.30	39	10	36
B291994		3.55	0.92	291	1	1.64	18	640	19	0.16	<5	498	0.31	40	20	38
B291995		3.67	0.92	221	<1	1.58	21	690	20	0.29	6	487	0.32	42	10	25
B291996		0.03	11.40	153	<1	0.01	<1	520	2	0.01	<5	106	<0.01	2	<10	6
B291997		3.06	0.61	468	1	0.45	18	580	189	0.87	89	201	0.26	38	30	355
B291998		3.31	1.06	353	1	1.76	15	660	22	0.11	<5	550	0.31	50	20	45
B291999		3.48	1.24	423	<1	1.78	11	660	24	0.08	<5	543	0.30	56	10	47
B292000		3.39	1.11	396	<1	1.90	13	590	28	0.08	<5	535	0.29	52	<10	49
B292001		3.34	1.06	455	1	1.71	10	600	27	0.11	5	480	0.28	51	<10	45
B292002		3.41	1.10	427	1	1.70	12	620	24	0.12	<5	473	0.29	54	<10	44
B292003		3.69	1.14	511	4	1.28	11	640	36	0.19	16	406	0.30	52	10	77
B292004		3.98	0.89	468	1	0.79	15	570	166	0.56	60	371	0.27	36	30	750
B292005		3.93	0.94	297	<1	1.56	18	630	29	0.20	11	468	0.29	41	10	39
B292006		3.31	0.68	1170	4	0.16	13	610	493	0.45	233	147	0.25	37	40	790
B292007		3.66	0.71	1025	5	0.17	16	620	1005	1.51	370	116	0.26	38	20	902
B292008		3.73	0.85	311	2	1.64	16	620	29	0.18	8	458	0.29	39	10	43
B292009																
B292010		3.28	0.38	71	2	0.09	9	330	29	0.02	156	144	0.23	106	10	17
B292011		3.77	0.92	329	5	1.77	14	670	28	0.17	<5	510	0.30	42	90	49
B292012		4.20	0.96	330	1	1.81	12	720	29	0.16	<5	519	0.29	44	60	42
B292013		4.51	0.89	280	2	1.70	16	650	23	0.16	7	530	0.29	42	30	37
B292014		3.86	0.97	309	<1	1.88	15	650	23	0.16	<5	537	0.31	44	10	41
B292015		3.74	1.02	340	3	1.72	16	730	25	0.26	7	497	0.33	52	10	43
B292016		0.04	11.35	160	<1	0.02	2	480	<2	0.02	<5	107	<0.01	2	<10	6
B292017		4.18	1.12	315	3	1.64	16	690	21	0.40	<5	453	0.32	52	20	38
B292018		3.78	1.10	362	11	1.77	14	690	22	0.16	<5	505	0.32	52	20	44
B292019		3.61	1.28	390	1	1.82	13	680	20	0.10	<5	530	0.32	59	30	49
B292020		3.71	1.25	371	1	1.88	14	640	23	0.17	<5	522	0.30	56	10	44
B292021		4.24	1.38	423	1	1.72	15	710	20	0.16	<5	516	0.33	62	120	47
B292022		4.14	1.36	417	1	1.78	17	710	19	0.21	<5	554	0.32	61	40	50
B292023		3.79	1.35	428	1	1.80	16	680	19	0.13	<5	564	0.32	59	40	50

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292024		6.46	0.199	<0.5	7.27	82	1370	3.0	<2	2.61	<0.5	10	49	19	2.70	0.01
B292025		6.00	0.023	<0.5	7.21	7	1370	2.7	<2	2.80	<0.5	10	46	14	2.68	0.01
B292026		6.42	0.157	<0.5	7.03	51	1310	2.8	6	2.55	<0.5	8	36	28	2.40	0.01
B292027		6.28	0.051	<0.5	7.16	24	1470	3.1	<2	2.59	<0.5	9	32	14	2.37	<0.01
B292028		5.52	0.016	<0.5	7.41	23	1520	3.1	<2	2.57	<0.5	8	32	19	2.48	<0.01
B292029		0.04	0.015													
B292030		0.10	1.450	<0.5	6.98	1240	690	5.9	<2	0.01	<0.5	5	198	38	3.61	0.05
B292031		5.72	0.055	<0.5	7.24	40	1440	2.9	<2	2.40	<0.5	6	29	23	2.30	0.01
B292032		6.98	0.403	<0.5	7.29	157	1410	2.9	3	2.16	<0.5	7	26	30	2.26	<0.01
B292033		5.90	0.186	<0.5	7.47	68	1470	3.0	10	2.47	<0.5	8	31	35	2.47	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049846

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292024		3.47	1.26	501	1	1.66	14	680	102	0.11	5	503	0.30	59	10	102
B292025		3.22	1.36	472	1	1.91	13	680	21	0.06	<5	553	0.31	59	<10	56
B292026		3.55	1.00	374	1	1.94	14	600	22	0.14	5	545	0.29	47	<10	50
B292027		3.38	0.92	383	<1	1.96	18	640	28	0.05	5	556	0.31	44	<10	66
B292028		3.57	0.97	372	1	1.84	18	670	26	0.10	<5	532	0.30	46	10	62
B292029																
B292030		2.74	0.34	87	2	0.11	20	320	22	0.01	113	90	0.27	92	10	41
B292031		3.48	0.92	346	1	1.82	15	630	34	0.09	<5	510	0.30	41	30	65
B292032		3.59	0.87	302	<1	1.92	15	610	28	0.12	5	528	0.29	39	<10	50
B292033		3.60	0.96	323	1	1.84	18	660	24	0.16	<5	554	0.30	44	10	52

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

CERTIFICATE VA05049598

Project: Dublin Gulch-1735

P.O. No.:

This report is for 216 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 24-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER


SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Au-GRA21	Au 30g FA-GRAV finish	WST-SIM

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3



This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
/01-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292708		6.02	0.088	<0.5	7.61	736	1480	3.3	3	2.49	<0.5	8	114	51	2.44	<0.01
B292709		<0.02	0.096													
B292710		0.10	0.093	<0.5	7.43	130	610	2.7	<2	0.54	<0.5	60	1220	416	9.00	0.02
B292711		5.68	0.124	<0.5	7.82	1165	1460	3.3	4	2.40	<0.5	10	92	52	2.42	<0.01
B292712		5.34	0.283	0.8	7.76	4300	1520	3.2	13	2.07	<0.5	11	121	96	2.71	<0.01
B292713		1.28	0.205	<0.5	8.15	2150	1570	3.5	<2	2.25	<0.5	9	95	55	2.52	<0.01
B292714		5.96	0.077	<0.5	8.19	903	1470	3.5	<2	2.21	<0.5	8	135	61	2.42	<0.01
B292715		4.84	0.050	<0.5	7.83	553	1430	3.4	<2	2.13	<0.5	8	96	62	2.35	<0.01
B292716		2.04	<0.005	0.5	0.22	12	20	<0.5	<2	19.15	<0.5	1	8	3	0.16	<0.01
B292717		4.00	0.065	<0.5	7.87	813	1520	3.4	<2	2.12	<0.5	8	90	44	2.19	<0.01
B292718		5.50	0.064	<0.5	7.91	692	1500	3.3	<2	2.27	<0.5	7	102	45	2.31	<0.01
B292719		4.74	0.081	<0.5	7.82	1115	1500	3.3	<2	2.23	<0.5	8	86	42	2.22	<0.01
B292720		4.38	0.117	0.6	7.74	1730	1460	3.3	<2	2.13	<0.5	9	120	55	2.33	<0.01
B292721		2.52	0.122	<0.5	7.50	1285	1320	3.3	2	2.27	<0.5	8	85	35	2.37	<0.01
B292722		2.22	0.133	<0.5	7.73	1180	1350	3.3	<2	2.33	<0.5	7	111	36	2.30	<0.01
B292723		5.92	0.195	<0.5	7.50	1265	1420	3.2	4	2.04	<0.5	8	82	36	2.34	<0.01
B292724		5.30	0.137	<0.5	7.84	1335	1310	3.6	<2	2.36	<0.5	7	121	31	2.37	<0.01
B292725		3.58	0.193	0.5	8.06	2020	1310	3.6	7	2.51	<0.5	7	97	45	2.52	<0.01
B292726		1.58	0.112	<0.5	8.12	2750	1380	3.8	3	2.39	<0.5	7	142	46	2.69	<0.01
B292727		4.46	0.110	<0.5	7.54	1775	1260	3.5	2	2.01	<0.5	7	96	38	2.33	<0.01
B292728		5.88	0.126	0.5	8.37	2330	1410	3.6	<2	2.41	<0.5	7	117	50	2.39	<0.01
B292729		<0.02	0.123													
B292730		0.10	0.424	3.0	9.83	14	1100	1.2	<2	1.52	<0.5	9	8	7500	3.36	0.02
B292731		5.20	0.159	0.6	7.80	3250	1380	3.6	6	2.25	<0.5	8	116	49	2.37	<0.01
B292732		1.92	0.182	<0.5	8.30	2130	1360	3.7	6	2.11	<0.5	8	90	55	2.48	<0.01
B292733		2.04	0.078	<0.5	7.46	968	1350	3.3	<2	2.21	<0.5	8	89	50	2.27	<0.01
B292734		3.08	0.211	0.7	7.71	2690	1370	3.2	8	2.26	<0.5	6	109	99	2.30	0.01
B292735		7.88	0.106	1.0	7.68	1730	1410	3.3	2	2.25	<0.5	9	97	57	2.33	<0.01
B292736		1.86	<0.005	<0.5	0.11	8	10	<0.5	<2	19.05	<0.5	<1	7	1	0.09	<0.01
B292737		4.02	0.056	0.7	7.17	555	1380	3.6	<2	2.15	<0.5	8	91	55	2.33	<0.01
B292738		5.76	0.187	0.7	6.97	2420	1220	3.4	5	2.47	<0.5	7	120	69	2.32	<0.01
B292739		4.96	0.288	0.6	7.08	3110	1100	3.5	8	2.11	<0.5	9	102	69	2.46	<0.01
B292740		6.70	0.096	<0.5	6.94	937	1220	3.4	8	2.01	<0.5	7	106	50	2.24	<0.01
B292741		1.74	0.033	<0.5	7.64	321	1400	3.7	2	2.27	<0.5	7	90	43	2.34	<0.01
B292742		1.36	0.030	<0.5	7.59	343	1350	3.6	<2	2.34	<0.5	7	125	43	2.32	<0.01
B292743		0.78	0.024	0.5	7.09	517	1400	3.4	2	2.55	<0.5	10	109	59	2.39	<0.01
B292744		3.78	0.136	0.5	6.48	578	1360	3.1	3	1.67	<0.5	6	100	49	2.07	<0.01
B292745		2.68	0.084	<0.5	7.35	896	1420	3.3	3	1.76	<0.5	7	91	58	2.17	<0.01
B292746		5.56	0.070	0.7	7.22	1215	1510	3.5	6	1.96	<0.5	10	112	74	2.28	<0.01
B292747		6.12	0.343	0.6	7.17	4850	1310	3.6	17	1.64	<0.5	10	101	127	2.78	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292708		3.67	0.89	207	1	1.70	20	640	20	0.41	<5	497	0.31	40	<10	24
B292709																
B292710		2.26	0.61	417	9	0.12	497	360	157	0.02	12	52	0.22	94	30	619
B292711		3.80	0.87	177	2	1.70	19	660	18	0.44	<5	499	0.31	40	10	24
B292712		4.09	0.86	138	2	1.57	17	640	14	0.65	5	460	0.30	39	10	32
B292713		3.83	0.87	154	<1	1.72	15	710	15	0.46	<5	494	0.30	40	20	25
B292714		3.88	0.83	164	3	1.71	18	640	18	0.41	<5	496	0.30	41	10	33
B292715		3.97	0.87	158	1	1.80	18	650	14	0.42	<5	493	0.31	42	10	20
B292716		0.04	11.30	176	<1	0.02	4	530	<2	0.01	<5	118	0.01	2	<10	8
B292717		3.89	0.83	153	1	1.65	19	660	14	0.35	<5	471	0.31	39	10	20
B292718		3.88	0.85	166	2	1.74	17	670	15	0.39	<5	481	0.32	43	10	20
B292719		3.90	0.78	154	2	1.68	18	620	12	0.38	<5	482	0.30	38	10	17
B292720		3.87	0.79	152	1	1.74	19	650	15	0.46	<5	482	0.31	38	<10	18
B292721		3.80	0.85	206	2	1.70	15	620	19	0.37	<5	482	0.29	39	10	24
B292722		3.85	0.84	201	1	1.69	15	630	21	0.35	<5	492	0.29	38	10	22
B292723		4.11	0.83	198	1	1.69	14	630	17	0.36	<5	473	0.30	41	10	23
B292724		3.82	0.89	209	1	1.66	13	600	22	0.38	<5	482	0.29	40	10	21
B292725		3.69	0.91	198	2	1.57	13	620	17	0.48	<5	466	0.29	42	10	21
B292726		4.01	0.92	208	2	1.69	12	630	21	0.54	<5	496	0.29	42	20	28
B292727		3.91	0.86	189	1	1.63	14	560	23	0.43	<5	462	0.27	37	10	29
B292728		4.08	0.99	175	3	1.73	13	640	10	0.47	<5	523	0.30	43	10	19
B292729																
B292730		3.69	1.21	506	3	3.45	10	2010	7	0.25	<5	715	0.35	173	10	50
B292731		4.31	0.97	174	2	1.78	14	630	9	0.48	<5	497	0.30	43	10	19
B292732		4.06	1.08	190	1	1.80	9	630	20	0.45	<5	492	0.29	43	<10	22
B292733		3.56	0.98	181	<1	1.65	15	620	13	0.40	<5	449	0.29	40	<10	22
B292734		4.05	0.82	136	2	1.36	13	610	30	0.78	9	354	0.28	40	10	20
B292735		3.98	0.93	153	1	1.73	17	640	13	0.52	5	516	0.30	40	10	29
B292736		0.03	11.00	155	<1	0.01	<1	510	<2	0.01	<5	102	<0.01	<1	<10	6
B292737		3.69	0.94	162	1	1.86	14	640	20	0.50	<5	451	0.30	43	10	26
B292738		3.69	0.86	150	2	1.57	14	610	26	0.64	6	390	0.28	40	10	54
B292739		3.79	0.81	148	<1	1.45	15	550	22	0.65	8	368	0.25	39	10	22
B292740		3.51	0.86	169	1	1.65	12	560	19	0.43	<5	443	0.27	40	10	26
B292741		3.59	0.86	198	<1	1.89	16	630	25	0.37	6	482	0.30	41	<10	31
B292742		3.45	0.85	203	1	1.85	15	590	22	0.35	<5	481	0.29	40	<10	34
B292743		3.66	0.89	201	1	1.76	20	620	18	0.45	<5	459	0.32	47	<10	34
B292744		3.67	0.93	152	1	1.66	16	540	16	0.43	<5	370	0.28	38	<10	19
B292745		3.88	0.87	132	2	1.59	16	600	12	0.58	<5	420	0.29	39	20	16
B292746		3.99	1.03	146	1	1.66	18	640	15	0.61	<5	427	0.31	42	20	17
B292747		4.07	1.14	128	3	0.55	18	560	37	0.79	27	192	0.25	38	30	25

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	Au-GRA21 / Au / ppm / 0.05
B292708 B292709 B292710 B292711 B292712		
B292713 B292714 B292715 B292716 B292717		
B292718 B292719 B292720 B292721 B292722		
B292723 B292724 B292725 B292726 B292727		
B292728 B292729 B292730 B292731 B292732		
B292733 B292734 B292735 B292736 B292737		
B292738 B292739 B292740 B292741 B292742		
B292743 B292744 B292745 B292746 B292747		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292748		2.94	0.420	0.7	7.36	5420	1220	2.8	24	1.90	<0.5	9	115	102	2.56	0.01
B292749		<0.02	0.422													
B292750		0.10	0.900	2.5	8.53	19	500	0.8	<2	2.12	0.7	26	113	2340	5.78	<0.01
B292751		3.90	0.264	<0.5	7.64	4860	1340	3.3	14	2.40	<0.5	7	83	81	2.62	0.01
B292752		3.00	0.304	<0.5	7.82	6080	1250	2.9	22	2.78	<0.5	8	114	85	2.82	0.01
B292753		2.30	0.221	1.1	7.45	5400	1400	2.9	11	2.12	<0.5	9	93	77	2.30	<0.01
B292754		6.00	0.274	1.0	7.89	8970	1270	2.9	13	2.55	<0.5	8	110	133	2.54	<0.01
B292755		6.02	0.150	0.5	7.73	3730	1480	3.4	6	2.37	<0.5	10	104	74	2.70	<0.01
B292756		2.08	<0.005	<0.5	0.10	16	20	<0.5	<2	19.70	<0.5	<1	5	1	0.09	<0.01
B292757		2.40	0.171	0.8	7.93	2570	1510	3.4	8	2.23	<0.5	7	99	75	2.79	<0.01
B292758		2.28	0.154	<0.5	7.61	8710	1160	2.9	7	2.00	<0.5	7	92	55	2.72	0.01
B292759		1.70	0.159	<0.5	7.89	2600	1310	2.9	4	2.10	<0.5	10	112	71	2.67	0.01
B292760		4.00	0.175	0.5	7.73	2850	960	3.1	9	4.05	4.1	6	86	56	2.94	0.05
B292761		1.22	0.035	<0.5	7.96	612	1670	3.3	<2	2.55	<0.5	7	102	29	2.67	<0.01
B292762		1.20	0.052	<0.5	7.82	999	1670	3.3	<2	2.60	<0.5	8	86	30	2.70	<0.01
B292763		5.94	0.102	<0.5	7.59	1085	1510	2.8	<2	2.35	<0.5	7	100	45	2.33	<0.01
B292764		4.40	0.025	<0.5	7.59	131	1520	2.7	<2	2.09	<0.5	5	71	18	2.23	0.01
B292765		1.96	0.199	0.7	7.61	3270	1110	3.0	2	2.52	<0.5	6	117	83	2.24	0.01
B292766		5.66	0.090	<0.5	7.76	1500	1360	3.7	4	1.95	<0.5	7	85	34	2.14	0.01
B292767		5.60	0.136	<0.5	7.75	2600	1410	3.2	12	2.14	<0.5	6	94	51	2.25	0.01
B292768		3.54	0.092	<0.5	7.84	1310	1330	3.4	5	3.82	<0.5	7	92	46	2.31	0.01
B292769		<0.02	0.090													
B292770		0.10	1.545	<0.5	7.55	1230	740	5.7	<2	0.01	<0.5	4	199	40	3.97	0.06
B292771		7.30	0.070	<0.5	7.62	605	1510	3.2	3	2.12	<0.5	6	85	50	2.37	0.01
B292772		3.62	0.074	<0.5	7.43	591	1410	3.2	6	1.78	<0.5	7	81	48	2.40	0.01
B292773		2.50	0.355	1.8	6.32	1240	150	2.6	16	3.46	4.2	5	97	103	5.94	0.06
B292774		5.04	0.114	0.7	7.80	1020	1050	3.2	2	2.87	0.5	7	94	74	3.23	0.01
B292775		4.12	0.126	<0.5	8.01	2090	1340	3.3	5	2.06	<0.5	10	137	58	2.77	0.01
B292776		Empty Bag														
B292777		<0.02	0.065	<0.5	8.15	729	1510	3.2	5	2.47	<0.5	8	99	53	2.75	0.01
B292778		5.44	0.038	<0.5	7.78	350	1450	3.5	<2	2.11	<0.5	7	101	29	2.41	0.01
B292779		5.10	0.060	<0.5	7.55	525	1380	2.9	3	2.27	<0.5	5	68	30	2.27	0.01
B292780		3.60	0.121	<0.5	7.55	1155	1210	3.1	2	2.25	<0.5	5	91	46	2.25	0.01
B292781		2.80	0.066	<0.5	7.41	827	1510	2.9	<2	2.35	<0.5	7	97	40	2.31	0.01
B292782		2.50	0.107	<0.5	7.52	1530	1400	2.8	4	2.37	<0.5	8	71	41	2.35	0.01
B292783		4.68	0.352	0.7	7.34	6580	1200	2.7	14	1.84	1.1	8	104	55	2.46	0.02
B292784		2.06	0.062	<0.5	7.96	1775	1440	3.3	5	1.86	<0.5	6	86	35	2.30	0.01
B292785		0.64	0.144	1.3	7.89	1725	630	2.7	6	2.59	2.6	5	115	46	2.34	0.04
B292786		1.28	0.371	0.8	7.32	6740	1310	3.0	24	2.33	<0.5	7	101	67	2.45	0.01
B292787		0.20	0.062	0.5	6.92	525	1150	3.3	2	1.83	1.0	7	139	38	1.82	0.02

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292748		3.98	0.97	146	2	0.56	15	580	72	0.84	32	202	0.26	38	40	49
B292749																
B292750		1.94	1.50	496	2	3.52	59	750	21	0.73	<5	238	0.34	102	<10	230
B292751		3.91	1.00	190	2	0.65	18	680	32	0.61	30	251	0.29	38	30	24
B292752		3.95	0.64	207	5	0.66	14	620	100	1.17	40	241	0.28	39	20	33
B292753		3.96	0.70	141	2	0.97	13	620	22	0.59	14	308	0.28	37	50	17
B292754		4.07	0.70	178	2	0.96	15	620	27	0.83	18	317	0.28	39	30	25
B292755		3.99	0.93	172	1	1.53	17	660	19	0.64	6	449	0.31	43	80	20
B292756		0.03	11.35	154	<1	0.01	1	490	<2	0.01	<5	108	<0.01	<1	<10	6
B292757		4.18	0.99	188	1	1.46	16	670	25	0.73	13	440	0.30	44	20	29
B292758		3.95	0.91	248	2	0.51	10	630	58	0.59	25	192	0.27	45	30	58
B292759		4.06	0.95	260	3	0.65	9	670	24	0.45	16	235	0.29	43	20	42
B292760		3.38	0.99	482	1	0.68	15	610	270	0.93	87	288	0.27	39	20	676
B292761		3.61	0.93	330	1	1.72	17	700	33	0.22	9	524	0.34	43	20	66
B292762		3.66	0.94	332	2	1.69	19	710	35	0.27	8	514	0.34	46	10	64
B292763		3.73	0.81	240	1	1.47	14	610	21	0.36	<5	463	0.29	36	10	38
B292764		3.19	0.80	255	1	1.75	18	590	26	0.18	7	450	0.25	30	10	35
B292765		3.99	0.75	412	1	0.73	16	510	72	0.50	23	226	0.23	29	20	150
B292766		4.07	0.78	213	1	1.70	15	550	29	0.28	6	446	0.26	31	10	31
B292767		4.06	0.90	190	2	1.64	15	600	24	0.41	<5	455	0.28	35	30	24
B292768		3.89	0.88	353	2	1.54	17	610	23	0.44	10	442	0.28	35	20	29
B292769																
B292770		2.72	0.37	93	3	0.11	18	320	32	0.02	124	96	0.22	86	10	46
B292771		4.08	0.92	291	2	1.74	15	640	20	0.41	11	478	0.30	36	30	25
B292772		3.95	0.91	324	1	1.41	14	630	35	0.39	17	394	0.28	37	20	33
B292773		2.86	0.84	1585	1	0.03	11	470	2260	4.69	1065	108	0.18	27	20	712
B292774		3.55	0.90	647	6	0.80	15	650	85	1.19	36	286	0.28	36	20	146
B292775		4.30	0.87	281	2	1.13	18	610	42	0.71	19	333	0.28	36	20	35
B292776																
B292777		4.03	1.05	273	2	1.59	13	670	25	0.52	8	483	0.31	45	20	36
B292778		3.98	0.90	308	2	1.44	12	680	29	0.31	10	427	0.30	38	20	48
B292779		3.54	0.88	334	1	1.49	11	660	31	0.22	10	436	0.26	32	20	38
B292780		3.98	0.80	399	3	0.90	13	590	39	0.43	19	315	0.27	36	20	51
B292781		4.03	1.05	348	2	1.24	16	630	22	0.28	15	372	0.28	37	20	25
B292782		3.80	1.05	349	2	1.20	16	620	24	0.37	17	357	0.27	36	20	23
B292783		4.19	0.71	459	1	0.85	14	590	138	0.68	68	254	0.25	33	20	190
B292784		4.17	0.80	281	2	1.42	15	590	35	0.28	19	408	0.28	36	10	39
B292785		3.92	0.88	1450	1	0.12	12	590	149	0.55	63	122	0.24	35	10	449
B292786		3.74	0.76	358	2	1.26	16	580	64	0.65	40	399	0.26	33	20	34
B292787		4.04	0.66	293	1	1.13	16	550	60	0.21	10	332	0.28	36	10	237

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	Au-GRA21 / Au / ppm / 0.05
B292748		
B292749		
B292750		
B292751		
B292752		
B292753		
B292754		
B292755		
B292756		
B292757		
B292758		
B292759		
B292760		
B292761		
B292762		
B292763		
B292764		
B292765		
B292766		
B292767		
B292768		
B292769		
B292770		
B292771		
B292772		
B292773		
B292774		
B292775		
B292776		
B292777		
B292778		
B292779		
B292780		
B292781		
B292782		
B292783		
B292784		
B292785		
B292786		
B292787		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292788		5.54	0.175	1.8	7.66	3780	980	2.8	8	2.46	4.3	9	83	60	2.44	0.06
B292789		<0.02	0.180													
B292790		0.10	3.28	<0.5	7.26	13	2090	3.3	<2	4.68	<0.5	23	135	93	5.12	0.01
B292791		5.08	0.151	1.6	7.56	2390	900	2.8	8	2.41	1.2	6	109	77	2.18	0.01
B292792		4.24	0.084	<0.5	7.79	854	1490	2.6	6	2.25	<0.5	5	59	47	2.29	0.01
B292793		1.84	0.175	5.9	7.01	4050	680	2.6	13	3.53	1.7	7	98	99	2.66	0.02
B292794		5.18	0.074	<0.5	7.60	875	1390	3.1	<2	2.36	<0.5	6	80	63	2.31	0.01
B292795		6.44	0.236	1.1	7.76	4820	1260	2.9	16	2.22	2.9	6	111	68	2.42	0.03
B292796		2.22	<0.005	<0.5	0.11	<5	20	<0.5	<2	19.30	<0.5	<1	5	1	0.10	<0.01
B292797		5.84	0.347	2.1	7.76	4840	800	2.8	14	2.24	0.9	9	110	81	3.10	0.02
B292798		5.90	0.231	<0.5	7.59	3020	1480	2.7	8	1.92	<0.5	6	70	68	2.50	0.01
B292799		5.94	0.048	<0.5	7.65	792	1450	3.2	2	1.90	<0.5	6	103	49	2.20	0.01
B292800		3.46	0.054	<0.5	7.46	728	1420	3.2	3	2.16	<0.5	6	74	27	2.25	0.01
B292801		2.46	0.357	1.1	7.78	6940	450	3.0	27	2.25	<0.5	10	90	68	4.03	0.01
B292802		2.58	0.407	0.8	8.21	2050	1340	3.2	7	2.44	<0.5	6	77	72	3.14	0.01
B292803		3.42	0.053	<0.5	7.01	644	1520	2.3	2	1.76	<0.5	4	72	40	1.94	<0.01
B292804		1.94	0.061	<0.5	7.20	966	1520	3.0	2	1.99	<0.5	5	69	42	1.98	<0.01
B292805		4.06	0.101	<0.5	7.26	1165	1550	3.2	5	2.21	<0.5	6	93	52	2.17	<0.01
B292806		3.38	0.311	0.5	6.97	5780	1430	3.0	10	1.94	<0.5	8	78	134	2.36	0.01
B292807		0.50	0.302	<0.5	7.30	>10000	1330	2.5	20	1.40	<0.5	9	112	87	2.53	<0.01
B292808		0.22	0.067	<0.5	7.34	1225	1700	3.0	2	2.04	<0.5	6	28	45	2.42	0.01
B292809		<0.02	0.076													
B292810		0.10	1.520	<0.5	7.14	1230	710	5.9	<2	0.01	<0.5	5	207	38	3.78	0.06
B292811		0.24	0.056	<0.5	8.11	559	1580	3.2	2	1.96	<0.5	6	29	36	2.48	0.01
B292812		1.10	0.140	1.3	7.00	2640	880	2.9	5	1.51	4.7	5	29	83	2.51	0.08
B292813		0.60	1.785	9.7	4.25	9520	20	1.7	15	1.44	6.1	8	51	82	17.50	0.12
B292814		3.50	0.118	<0.5	7.06	1950	1320	2.4	5	2.12	<0.5	5	28	30	2.47	0.01
B292815		6.04	0.138	3.7	6.64	1890	760	3.2	12	2.01	9.3	6	56	58	2.43	0.18
B292816		1.86	<0.005	<0.5	0.12	10	20	<0.5	<2	19.10	<0.5	1	3	3	0.11	<0.01
B292817		5.82	0.195	0.6	7.22	4150	1330	3.0	20	2.02	3.8	5	29	64	2.35	0.06
B292818		6.26	0.171	1.1	7.10	3350	1300	2.9	11	2.06	2.2	7	56	67	2.73	0.03
B292819		5.96	0.189	0.7	7.19	2740	1280	2.9	13	2.14	0.9	8	31	61	2.38	0.02
B292820		4.78	0.160	1.9	6.95	3580	900	2.8	9	2.70	9.6	7	56	74	2.56	0.14
B292821		2.44	0.466	2.5	6.71	>10000	600	2.5	22	2.04	7.2	6	19	62	3.23	0.08
B292822		2.30	0.772	4.5	6.42	>10000	500	2.4	45	1.92	4.1	5	56	65	4.25	0.04
B292823		3.72	0.340	0.9	6.95	5990	810	2.4	19	2.15	<0.5	8	25	56	3.50	0.01
B292824		2.68	0.266	0.6	7.09	6780	1390	2.9	15	2.01	<0.5	13	64	70	2.41	0.01
B292825		3.60	0.470	<0.5	6.69	>10000	1410	2.0	31	1.80	<0.5	8	25	22	2.16	0.01
B292826		5.14	0.155	<0.5	7.55	3730	1420	3.3	10	2.14	<0.5	7	52	48	2.08	0.01
B292827		1.78	0.179	0.6	7.59	3130	1490	3.0	12	1.93	3.3	9	27	63	2.65	0.05

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292788		4.15	0.78	936	2	0.51	16	600	232	0.60	53	220	0.26	35	20	723
B292789																
B292790		3.49	2.99	1025	13	2.36	63	2300	32	0.31	5	1680	0.37	162	10	94
B292791		3.77	0.90	733	2	0.62	15	640	69	0.40	27	238	0.28	35	30	236
B292792		3.46	0.91	321	2	1.46	14	640	28	0.39	18	420	0.25	32	20	18
B292793		3.51	0.75	1490	1	0.27	13	540	535	0.92	295	204	0.23	31	10	339
B292794		4.16	0.80	473	1	1.03	16	630	54	0.40	22	338	0.28	37	20	65
B292795		4.17	0.75	563	2	0.78	15	620	166	0.76	65	284	0.27	35	20	483
B292796		0.03	11.60	154	<1	0.01	1	500	2	0.01	<5	110	<0.01	2	<10	7
B292797		4.09	0.69	558	4	0.67	15	610	244	1.70	89	262	0.26	35	20	194
B292798		3.74	0.97	271	2	1.41	14	610	30	0.51	15	413	0.25	31	20	27
B292799		4.11	0.92	234	2	1.59	16	590	26	0.28	6	434	0.28	34	30	31
B292800		3.85	0.89	273	2	1.70	13	610	25	0.23	<5	493	0.29	35	10	36
B292801		3.96	0.81	293	2	1.43	19	610	81	2.37	21	462	0.28	34	30	38
B292802		4.03	0.87	306	2	1.62	15	640	53	1.29	10	517	0.30	36	10	44
B292803		3.45	1.03	267	1	1.18	11	600	21	0.20	7	367	0.22	27	10	18
B292804		4.25	0.88	215	1	1.37	13	600	18	0.35	<5	429	0.28	33	10	17
B292805		4.05	0.90	221	2	1.65	14	620	19	0.37	5	490	0.29	34	20	18
B292806		4.22	0.85	223	2	1.32	14	600	30	0.64	22	382	0.27	34	20	29
B292807		4.60	0.69	159	2	1.24	14	610	19	0.79	19	333	0.25	33	10	13
B292808		4.25	0.81	226	3	1.62	15	660	19	0.37	13	499	0.29	35	50	22
B292809																
B292810		2.71	0.35	89	3	0.11	18	320	28	0.02	117	91	0.23	86	10	44
B292811		3.95	0.93	240	1	1.56	12	670	25	0.29	12	463	0.30	40	10	36
B292812		3.70	0.73	704	2	0.64	12	620	263	1.11	125	203	0.25	37	20	788
B292813		2.00	0.50	1365	1	0.02	8	410	3750	>10.0	1195	69	0.13	24	10	1195
B292814		3.24	0.86	514	1	1.00	8	600	73	0.32	29	373	0.22	33	10	52
B292815		3.65	0.72	962	1	0.30	11	570	466	0.71	44	158	0.25	35	10	1515
B292816		0.04	11.40	162	<1	0.01	<1	500	4	0.01	<5	108	<0.01	2	<10	9
B292817		4.14	0.91	476	1	1.03	12	600	282	0.50	121	350	0.27	37	20	588
B292818		3.96	0.81	425	2	1.04	14	610	170	1.04	48	357	0.27	37	20	389
B292819		4.20	0.87	498	1	0.96	10	600	76	0.55	33	353	0.27	39	30	196
B292820		3.97	0.89	1540	2	0.23	12	610	400	0.74	136	166	0.25	39	20	1500
B292821		3.29	0.70	1060	1	0.04	8	460	330	1.62	141	90	0.19	28	30	1095
B292822		3.03	0.68	1045	2	0.03	8	470	412	2.64	158	83	0.18	27	30	621
B292823		4.42	0.76	427	1	0.76	16	570	162	2.05	72	314	0.25	32	30	45
B292824		4.74	0.88	353	2	0.95	14	620	43	0.56	24	358	0.28	39	30	27
B292825		4.60	0.65	320	2	0.57	12	520	47	0.60	29	281	0.21	28	40	31
B292826		4.44	0.78	249	1	1.38	11	590	31	0.39	14	447	0.26	32	20	25
B292827		4.28	0.64	360	2	1.10	13	610	575	1.48	264	413	0.27	32	30	568

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method Analyte Units LOR	Au-GRA21 Au ppm 0.05
B292788 B292789 B292790 B292791 B292792		
B292793 B292794 B292795 B292796 B292797		
B292798 B292799 B292800 B292801 B292802		
B292803 B292804 B292805 B292806 B292807		
B292808 B292809 B292810 B292811 B292812		
B292813 B292814 B292815 B292816 B292817		
B292818 B292819 B292820 B292821 B292822		
B292823 B292824 B292825 B292826 B292827		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
/01-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B292828		1.98	0.065	1.9	7.97	1220	880	3.2	<2	2.44	2.1	6	52	84	1.88	0.04
B292829		<0.02	0.060													
B292830		0.10	2.83	<0.5	7.88	2180	780	13.5	<2	0.02	<0.5	<1	149	104	3.59	0.08
B292831		3.34	0.198	1.7	7.20	3700	990	2.9	10	1.99	<0.5	8	23	73	2.08	0.01
B292832		2.76	0.233	4.2	7.12	3250	720	2.4	14	2.78	0.8	8	50	76	2.91	0.02
B292833		1.14	0.729	3.5	6.44	4300	130	3.2	16	2.08	4.4	10	22	74	5.42	0.10
B292834		4.60	0.122	1.3	7.32	2140	680	2.7	4	2.48	1.8	7	53	64	2.58	0.03
B292835		3.98	0.085	<0.5	7.66	1115	1460	3.2	2	2.09	<0.5	8	27	54	2.06	<0.01
B292836		1.88	<0.005	<0.5	0.13	9	20	<0.5	<2	19.35	<0.5	1	5	2	0.12	<0.01
B292837		4.70	0.091	<0.5	7.82	1780	1460	2.9	3	2.18	<0.5	6	49	56	1.90	0.01
B292838		7.00	0.107	<0.5	7.18	1780	1410	3.1	4	1.92	<0.5	7	25	57	1.83	0.01
B292839		6.34	0.076	<0.5	7.29	1455	1490	3.3	4	1.92	<0.5	6	52	49	1.94	0.01
B292840		5.78	0.186	<0.5	7.15	4280	1450	3.1	14	2.02	<0.5	8	33	72	2.29	<0.01
B292841		3.14	0.198	<0.5	7.64	3270	1420	3.2	13	2.00	<0.5	6	57	61	2.25	0.01
B292842		3.28	0.190	<0.5	7.60	4160	1450	3.2	16	1.93	<0.5	5	27	48	2.27	0.01
B292843		5.08	0.165	<0.5	7.35	2740	1440	3.1	15	2.01	<0.5	7	58	55	2.06	0.01
B292844		4.28	0.410	<0.5	7.37	4800	1440	3.1	17	1.82	<0.5	7	27	38	2.10	0.01
B292845		2.20	0.807	<0.5	7.23	>10000	1470	2.6	38	1.41	<0.5	10	58	29	2.58	0.01
B292846		5.38	0.186	<0.5	7.54	4040	1420	3.1	6	2.04	<0.5	7	25	38	2.17	0.01
B292847		4.78	0.116	<0.5	7.55	1245	1350	3.3	6	2.20	<0.5	6	53	33	2.03	0.01
B292848		4.44	0.052	<0.5	7.47	761	1500	3.1	3	1.87	<0.5	5	23	26	1.96	0.01
B292849		<0.02	0.052													
B292850		0.10	0.094	<0.5	6.91	107	560	2.6	<2	0.50	<0.5	57	1125	373	8.07	0.03
B292851		2.36	0.042	<0.5	7.61	526	1490	3.5	<2	2.26	<0.5	6	96	34	2.11	0.01
B292852		5.16	0.038	<0.5	6.91	368	1380	3.2	<2	2.19	<0.5	6	106	29	1.84	0.01
B292853		1.98	0.064	0.5	7.68	603	1150	3.3	<2	2.78	1.3	7	112	29	2.36	0.03
B292854		4.82	0.038	<0.5	7.80	402	1200	3.3	<2	2.40	1.2	7	120	33	2.28	0.03
B292855		2.42	0.080	<0.5	7.24	569	1450	3.1	2	2.29	<0.5	7	96	30	2.20	0.01
B292856		2.52	<0.005	<0.5	0.08	5	10	<0.5	<2	18.20	<0.5	<1	7	1	0.09	0.01
B292857		2.88	0.333	<0.5	6.99	4540	1280	2.7	12	2.06	<0.5	9	106	36	2.32	0.01
B292858		5.26	0.077	0.5	7.59	512	1370	2.9	5	2.60	2.1	8	120	49	2.44	0.04
B292859		3.76	0.017	<0.5	7.37	66	1440	2.8	<2	2.45	<0.5	6	101	22	2.34	0.01
B292860		1.88	0.027	0.8	7.12	139	890	2.7	<2	4.88	1.3	4	126	26	2.16	0.04
B292861		1.72	0.019	<0.5	7.94	118	1560	2.9	<2	2.40	<0.5	6	100	24	2.40	0.01
B292862		1.48	0.022	<0.5	7.71	194	1560	2.8	<2	2.21	<0.5	7	114	26	2.26	0.02
B292863		2.80	0.047	<0.5	7.38	377	1580	3.0	4	2.10	<0.5	6	96	33	2.28	0.01
B292864		3.94	0.033	<0.5	7.54	248	1590	2.8	3	2.34	<0.5	7	116	33	2.37	0.02
B292865		3.34	0.033	0.9	7.53	271	1180	2.6	<2	2.34	1.3	5	97	32	2.22	0.03
B292866		5.48	0.106	0.5	7.39	479	1210	2.6	3	2.40	<0.5	6	108	42	2.23	0.03
B292867		4.08	0.110	<0.5	7.69	923	1570	2.9	<2	2.22	<0.5	7	103	35	2.34	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292828		3.91	0.73	1320	2	0.20	12	620	272	0.33	63	155	0.25	34	20	399
B292829																
B292830		3.35	0.40	73	3	0.09	10	350	32	0.02	164	149	0.23	103	20	16
B292831		4.06	0.65	762	1	0.43	13	580	94	0.58	35	225	0.25	32	30	64
B292832		3.76	0.64	1255	2	0.07	12	540	236	1.86	66	122	0.21	28	30	174
B292833		3.82	0.57	871	1	0.04	17	460	275	4.89	83	86	0.23	31	20	898
B292834		3.59	0.86	1795	2	0.04	14	560	347	1.00	115	97	0.23	30	30	333
B292835		4.41	0.74	219	2	1.41	12	630	22	0.46	9	423	0.28	34	50	15
B292836		0.03	11.50	144	<1	0.01	3	490	2	0.01	<5	106	0.01	2	<10	8
B292837		4.78	0.84	209	2	1.24	13	610	25	0.34	9	371	0.27	33	70	18
B292838		4.47	0.80	144	3	1.42	12	590	21	0.40	5	430	0.27	32	40	13
B292839		4.15	0.81	128	2	1.71	13	610	20	0.40	<5	524	0.28	33	20	14
B292840		4.14	0.86	120	1	1.59	14	630	18	0.57	<5	501	0.29	36	30	13
B292841		3.83	0.91	142	2	1.65	15	610	15	0.47	<5	545	0.29	36	10	16
B292842		3.95	0.87	138	2	1.63	14	620	14	0.46	<5	537	0.29	36	10	16
B292843		4.05	0.90	140	3	1.55	14	640	13	0.41	<5	504	0.29	35	20	14
B292844		4.39	0.85	135	2	1.46	14	620	17	0.43	<5	457	0.29	35	40	15
B292845		4.31	0.82	104	2	1.23	13	580	29	0.77	13	374	0.24	32	30	13
B292846		4.03	0.80	163	3	1.56	12	620	19	0.43	<5	478	0.28	34	50	22
B292847		3.78	0.81	183	1	1.55	13	600	16	0.29	<5	461	0.28	35	10	22
B292848		4.10	1.03	205	1	1.29	11	610	14	0.20	6	433	0.27	33	30	18
B292849																
B292850		2.16	0.56	368	9	0.12	467	340	142	0.02	10	50	0.21	89	30	584
B292851		4.01	0.85	188	1	1.72	18	660	20	0.31	<5	509	0.31	37	10	27
B292852		4.13	0.77	204	2	1.57	16	620	22	0.28	<5	482	0.29	36	60	28
B292853		3.93	0.84	453	3	0.90	15	650	116	0.55	23	267	0.29	36	20	250
B292854		3.96	0.80	380	2	1.11	14	670	33	0.45	20	318	0.30	39	50	240
B292855		3.96	0.70	287	4	1.34	19	630	20	0.39	12	415	0.30	37	20	38
B292856		0.03	10.85	141	<1	0.01	5	460	<2	0.01	<5	100	<0.01	2	<10	6
B292857		3.65	0.70	255	4	0.71	20	580	58	0.64	33	262	0.26	32	80	42
B292858		3.79	0.72	379	3	0.79	23	640	167	0.67	55	300	0.29	36	20	355
B292859		3.53	0.75	290	2	1.18	25	600	36	0.28	8	372	0.29	36	20	76
B292860		3.22	0.62	718	2	0.29	18	550	112	0.32	21	257	0.25	31	10	251
B292861		4.01	0.84	279	4	1.02	20	650	17	0.20	7	368	0.31	37	30	44
B292862		3.87	0.78	257	3	1.06	21	610	18	0.24	9	359	0.30	36	20	48
B292863		3.82	0.82	256	8	1.05	21	620	24	0.29	9	357	0.30	36	30	41
B292864		3.81	0.80	316	2	0.85	22	620	18	0.26	11	354	0.30	36	50	31
B292865		4.26	0.78	509	2	0.17	19	600	153	0.49	19	155	0.26	33	10	230
B292866		4.22	0.89	388	4	0.17	19	590	54	0.48	20	183	0.25	33	20	80
B292867		3.62	0.75	201	2	1.53	23	620	21	0.31	<5	473	0.30	37	20	35

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	Au-GRA21 / Au / ppm / 0.05
B292828		
B292829		
B292830		
B292831		
B292832		
B292833		
B292834		
B292835		
B292836		
B292837		
B292838		
B292839		
B292840		
B292841		
B292842		
B292843		
B292844		
B292845		
B292846		
B292847		
B292848		
B292849		
B292850		
B292851		
B292852		
B292853		
B292854		
B292855		
B292856		
B292857		
B292858		
B292859		
B292860		
B292861		
B292862		
B292863		
B292864		
B292865		
B292866		
B292867		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292868		6.34	0.091	<0.5	8.05	1615	1590	3.0	4	2.15	<0.5	7	128	25	2.30	0.02
B292869		<0.02	0.096													
B292870		0.10	3.20	0.5	8.59	8	2390	4.0	<2	5.44	<0.5	28	166	117	5.86	0.01
B292871		2.66	0.072	<0.5	7.64	241	1550	2.8	4	2.52	<0.5	7	110	37	2.13	0.01
B292872		3.44	0.086	<0.5	7.18	579	1520	2.6	3	2.53	<0.5	6	117	37	2.18	0.01
B292873		6.16	0.094	<0.5	6.43	963	1300	2.3	5	1.70	<0.5	6	90	40	1.85	0.01
B292874		6.14	0.058	<0.5	7.41	689	1620	2.7	3	2.14	<0.5	8	115	36	2.14	0.01
B292875		3.84	0.100	<0.5	7.27	2370	1520	2.8	6	2.28	<0.5	9	106	41	2.25	0.01
B292876		2.10	<0.005	<0.5	0.12	<5	10	<0.5	<2	17.65	<0.5	<1	8	1	0.10	0.01
B292877		2.96	0.169	<0.5	7.28	2480	1580	2.6	9	1.73	<0.5	7	104	46	2.02	0.01
B292878		1.38	0.407	<0.5	6.73	>10000	1080	2.3	7	2.36	<0.5	12	144	24	2.64	0.02
B292879		4.36	0.035	<0.5	7.37	335	1530	2.8	2	2.43	<0.5	9	97	40	2.30	0.01
B292880		2.42	0.367	<0.5	7.47	7360	1530	2.2	6	1.76	<0.5	8	120	51	2.28	0.02
B292881		0.52	0.213	<0.5	6.25	7810	1220	1.8	2	2.85	<0.5	9	114	23	1.88	0.02
B292882		0.68	0.166	<0.5	7.08	4270	1380	2.1	3	1.50	<0.5	6	146	22	1.83	0.02
B292883		1.92	>10.0	24.5	7.45	>10000	230	2.5	134	2.34	7.1	14	100	394	4.68	0.24
B292884		1.52	0.376	0.6	7.09	>10000	1060	2.3	10	2.12	<0.5	20	148	36	3.35	0.02
B292885		3.98	0.123	<0.5	7.64	1515	1690	2.8	4	2.52	<0.5	8	104	36	2.46	0.01
B292886		3.94	0.072	<0.5	8.12	484	1810	2.9	3	2.08	<0.5	10	136	31	2.73	0.02
B292887		6.40	0.156	<0.5	7.80	3200	1210	1.8	5	0.56	<0.5	11	122	44	2.47	0.09
B292888		0.26	0.056	<0.5	0.48	3720	30	<0.5	<2	0.05	<0.5	6	371	3	0.87	0.04
B292889		<0.02	0.052													
B292890		0.10	4.51	9.0	8.05	20	490	0.9	<2	2.79	1.3	19	23	127	4.21	0.01
B292891		4.64	0.090	0.5	9.01	1840	1390	2.0	3	0.35	1.1	11	94	39	2.13	0.11
B292892		2.24	0.093	<0.5	8.48	892	1960	3.0	<2	2.35	<0.5	9	122	20	2.74	0.02
B292893		3.96	0.143	<0.5	7.10	3920	1680	2.4	4	6.09	<0.5	8	63	19	3.09	0.02
B292894		3.18	0.141	0.5	8.39	1755	1570	3.0	<2	2.95	<0.5	10	136	72	2.97	0.02
B292895		4.94	0.080	<0.5	7.53	691	1760	2.9	<2	2.59	<0.5	10	99	31	2.74	<0.01
B292896		2.36	<0.005	<0.5	0.11	9	20	<0.5	<2	18.80	<0.5	<1	7	1	0.10	0.01
B292897		1.82	0.276	<0.5	8.63	9870	1700	3.0	13	2.65	<0.5	15	111	68	3.44	0.01
B292898		4.22	0.075	<0.5	8.53	563	1600	3.0	2	3.13	<0.5	10	119	70	3.13	0.01
B292899		3.70	0.187	1.1	7.43	6230	1040	2.5	4	2.64	0.9	14	136	103	3.47	0.02
B292900		1.60	0.922	<0.5	5.66	>10000	610	1.9	14	3.77	0.8	21	170	19	3.69	0.02
B292901		2.60	0.563	<0.5	8.05	6940	1590	2.7	9	2.38	<0.5	10	114	56	2.86	0.01
B292902		2.30	0.724	<0.5	8.13	7670	1630	2.8	10	2.35	<0.5	11	144	65	2.96	0.01
B292903		2.90	0.182	<0.5	8.49	1545	1540	3.5	10	3.53	<0.5	14	154	94	4.24	<0.01
B292904		1.68	0.165	<0.5	7.92	1585	1500	2.9	4	2.88	<0.5	7	126	45	2.84	0.01
B292905		6.28	0.643	<0.5	7.45	5480	1570	2.7	5	2.16	<0.5	11	104	60	2.78	<0.01
B292906		1.78	0.298	<0.5	7.89	5520	1540	3.1	<2	2.40	<0.5	16	130	23	2.87	0.01
B292907		2.14	3.22	<0.5	7.97	>10000	1420	2.9	28	2.66	<0.5	32	162	55	5.50	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292868		3.61	0.75	188	2	1.52	22	650	14	0.33	<5	479	0.32	39	10	29
B292869																
B292870		4.11	3.39	1210	16	2.77	78	2790	30	0.35	6	2000	0.45	197	<10	111
B292871		3.80	0.87	206	3	1.14	23	620	16	0.30	<5	423	0.30	36	50	30
B292872		3.65	0.89	203	2	1.13	22	610	15	0.34	<5	412	0.30	36	40	27
B292873		3.72	0.71	159	4	0.98	18	520	15	0.42	<5	290	0.25	30	100	23
B292874		3.60	0.67	192	2	1.39	23	630	17	0.35	<5	439	0.31	36	20	30
B292875		3.40	0.76	171	2	1.26	22	640	14	0.40	<5	415	0.30	37	70	28
B292876		0.03	10.55	142	<1	0.01	6	520	<2	0.01	<5	102	<0.01	3	<10	7
B292877		3.37	0.73	126	3	1.23	22	610	17	0.44	<5	392	0.29	34	110	25
B292878		3.24	0.62	171	4	0.90	20	530	21	1.10	14	254	0.24	30	790	27
B292879		3.73	0.72	231	2	1.15	24	650	16	0.38	7	393	0.32	39	30	31
B292880		3.95	0.64	191	4	0.63	18	620	15	0.63	18	277	0.27	35	220	16
B292881		2.88	0.50	269	1	0.15	17	520	32	0.62	27	208	0.24	30	30	31
B292882		3.21	0.53	229	2	0.15	17	580	22	0.38	19	196	0.27	34	30	33
B292883		3.40	0.87	753	2	0.33	24	620	1765	2.72	187	210	0.26	36	20	1055
B292884		3.40	0.62	215	2	0.85	25	570	42	1.24	20	325	0.24	33	20	77
B292885		3.61	0.77	241	3	1.25	23	690	14	0.42	6	420	0.33	40	30	27
B292886		3.40	0.81	236	6	1.25	23	710	15	0.43	7	442	0.34	42	20	33
B292887		2.80	0.48	371	3	0.12	28	670	16	0.35	8	172	0.32	42	110	29
B292888		0.07	0.03	31	1	0.05	10	30	92	0.21	10	8	0.01	4	10	13
B292889																
B292890		2.40	1.37	984	14	1.73	13	950	24	0.70	<5	438	0.38	156	<10	99
B292891		2.79	0.39	336	2	0.16	29	820	76	0.21	8	182	0.38	50	70	192
B292892		3.59	0.90	232	2	1.62	25	770	11	0.31	<5	582	0.38	47	20	30
B292893		3.68	1.30	562	1	0.67	20	670	15	0.38	5	394	0.29	39	20	25
B292894		3.34	0.95	324	4	1.33	25	770	36	0.46	<5	429	0.37	49	40	71
B292895		3.39	0.95	265	2	1.58	29	780	15	0.34	<5	517	0.38	48	20	39
B292896		0.03	11.15	141	1	0.01	7	490	<2	0.01	<5	106	<0.01	2	<10	7
B292897		3.25	1.13	204	3	1.70	38	850	16	0.95	9	532	0.40	54	70	31
B292898		3.33	1.16	331	3	1.65	37	890	29	0.54	<5	544	0.42	62	50	62
B292899		3.16	1.31	561	2	0.64	31	770	895	0.76	445	271	0.36	73	70	192
B292900		2.39	1.14	554	2	0.44	27	570	33	1.11	30	186	0.20	47	120	156
B292901		3.74	1.03	205	9	1.40	15	630	21	0.46	14	446	0.27	48	40	23
B292902		3.83	1.05	199	5	1.41	14	630	25	0.54	10	452	0.28	51	50	22
B292903		3.06	1.91	514	3	1.66	31	830	15	0.57	<5	550	0.40	80	50	57
B292904		3.49	1.31	289	2	1.66	15	690	20	0.28	<5	524	0.32	52	20	36
B292905		3.86	1.02	202	3	1.37	15	650	19	0.49	<5	442	0.27	50	40	32
B292906		3.76	0.99	286	2	1.19	11	610	23	0.42	6	412	0.27	51	20	42
B292907		2.76	1.65	316	2	1.18	34	850	12	1.34	12	366	0.38	83	30	42

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method Analyte Units LOR	Au-GRA21 Au ppm 0.05
B292868 B292869 B292870 B292871 B292872		
B292873 B292874 B292875 B292876 B292877		
B292878 B292879 B292880 B292881 B292882		
B292883 B292884 B292885 B292886 B292887		22.8
B292888 B292889 B292890 B292891 B292892		
B292893 B292894 B292895 B292896 B292897		
B292898 B292899 B292900 B292901 B292902		
B292903 B292904 B292905 B292906 B292907		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292908		3.22	0.334	<0.5	8.13	8340	1240	2.6	4	3.53	<0.5	19	165	71	4.56	0.03
B292909		<0.02	0.333													
B292910		0.10	1.450	<0.5	7.27	1290	700	6.2	<2	0.01	<0.5	5	201	39	3.75	0.05
B292911		3.06	0.140	<0.5	8.28	2710	1150	3.2	6	3.02	<0.5	14	174	136	3.94	0.01
B292912		5.40	0.139	<0.5	5.81	785	840	1.7	5	1.30	<0.5	10	210	72	2.87	0.02
B292913		2.32	0.179	<0.5	3.82	4570	350	0.9	7	1.94	<0.5	7	126	35	1.80	0.01
B292914		5.06	0.082	<0.5	4.34	546	420	1.4	3	1.96	<0.5	6	182	52	2.11	0.03
B292915		5.14	0.015	<0.5	4.65	317	410	1.2	<2	0.68	<0.5	6	120	55	2.13	0.01
B292916		2.28	<0.005	<0.5	0.10	42	10	<0.5	<2	18.90	<0.5	<1	6	1	0.10	0.01
B292917		3.16	0.014	<0.5	2.91	521	260	0.6	<2	0.69	<0.5	4	132	22	0.95	0.01
B292918		2.58	<0.005	<0.5	2.31	118	140	0.5	<2	0.64	<0.5	2	138	11	0.78	<0.01
B292919		5.60	0.012	<0.5	7.90	140	770	2.5	<2	1.54	<0.5	12	146	96	3.37	0.01
B292920		3.38	0.048	<0.5	8.17	1420	760	2.5	<2	1.57	<0.5	16	131	85	3.41	<0.01
B292921		3.28	0.019	<0.5	9.16	642	940	2.8	<2	1.23	<0.5	16	147	86	4.02	0.02
B292922		3.26	0.010	<0.5	8.00	411	780	2.4	<2	1.51	<0.5	15	97	74	3.65	0.01
B292923		3.06	0.011	<0.5	6.50	283	570	1.7	<2	0.55	<0.5	9	121	43	2.03	0.06

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292908		2.70	2.44	483	3	1.03	37	830	12	0.65	8	401	0.40	88	40	55
B292909																
B292910		2.80	0.35	90	3	0.11	21	330	26	0.02	116	93	0.26	94	10	46
B292911		2.33	1.61	286	2	1.70	31	990	6	0.88	5	513	0.39	80	40	38
B292912		2.89	0.99	263	2	0.75	27	330	7	0.73	<5	149	0.27	58	10	32
B292913		1.60	0.47	235	1	0.65	18	250	6	0.43	<5	142	0.17	30	40	15
B292914		1.92	0.81	335	4	0.43	18	410	4	0.44	<5	180	0.21	58	20	24
B292915		2.34	0.77	173	3	0.44	20	280	4	0.44	<5	82	0.16	39	<10	26
B292916		0.03	11.35	156	<1	0.01	3	480	5	0.02	<5	112	<0.01	2	<10	7
B292917		1.56	0.29	121	1	0.33	11	190	10	0.16	<5	73	0.10	17	10	11
B292918		1.00	0.32	101	1	0.30	7	170	8	0.07	<5	63	0.08	12	<10	7
B292919		3.78	1.34	354	4	0.72	37	610	6	0.88	<5	189	0.29	95	<10	30
B292920		4.10	1.42	424	5	0.70	39	630	11	0.86	<5	188	0.31	104	830	42
B292921		4.66	1.45	462	6	0.53	49	680	14	1.11	10	166	0.35	118	60	50
B292922		4.00	1.38	446	6	0.40	38	700	25	0.94	12	156	0.31	104	280	56
B292923		3.08	0.67	193	2	0.15	24	310	11	0.47	19	85	0.19	53	10	60

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05049598

Sample Description	Method / Analyte / Units / LOR	Au-GRA21 / Au / ppm / 0.05
B292908 B292909 B292910 B292911 B292912		
B292913 B292914 B292915 B292916 B292917		
B292918 B292919 B292920 B292921 B292922		
B292923		

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-JUL-2005
Account: STRGOL

CERTIFICATE VA05051469

Project: Dublin Gulch-1735

P.O. No.:

This report is for 40 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 29-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05051469

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292175		6.02	0.012		<0.5	7.53	227	1350	3.2	<2	1.98	<0.5	6	77	35	2.07
B292176		2.10	<0.005		<0.5	0.12	<5	10	<0.5	<2	20.1	<0.5	<1	8	7	0.14
B292177		5.38	0.015		<0.5	7.06	594	1560	3.3	<2	2.43	<0.5	8	80	50	2.32
B292178		9.56	0.049		<0.5	7.22	201	1390	3.1	7	2.20	<0.5	7	88	43	2.27
B292179		4.70	0.080		0.5	6.42	458	1420	1.5	9	2.17	<0.5	8	78	65	1.24
B292180		1.84	0.014		<0.5	7.22	63	1560	3.2	<2	1.77	<0.5	9	92	39	2.23
B292181		2.90	0.017		<0.5	6.73	86	970	1.7	<2	1.86	<0.5	2	80	25	1.00
B292182		2.58	0.010		<0.5	6.55	74	880	1.5	<2	1.68	<0.5	2	68	16	0.63
B292183		2.26	0.005		<0.5	7.14	63	1360	3.2	<2	2.46	<0.5	8	94	34	2.46
B292184		6.16	1.995		1.0	7.48	336	1440	3.2	164	2.18	<0.5	14	94	94	2.49
B292185		5.98	0.014		0.7	7.11	154	1480	3.2	<2	2.16	<0.5	8	92	70	2.27
B292186		0.56	0.046		<0.5	6.73	30	1450	3.1	11	2.14	<0.5	10	100	62	2.42
B292187		11.00	0.019		0.7	7.13	168	1440	3.1	<2	2.21	<0.5	8	84	61	2.23
B292188		6.32	0.022		0.5	6.83	212	1500	3.0	<2	2.38	<0.5	7	83	41	2.34
B292189		<0.02	0.017													
B292190		0.10	0.861		2.4	6.03	8	370	0.7	<2	1.62	1.0	22	96	2000	4.73
B292191		6.46	0.009		<0.5	7.12	190	1760	3.1	<2	2.80	<0.5	8	86	42	2.36
B292192		6.12	0.008		<0.5	7.97	168	1810	3.4	<2	2.72	<0.5	10	91	20	2.60
B292193		5.98	0.052		<0.5	7.62	1025	1590	3.1	<2	2.99	<0.5	11	82	59	2.68
B292194		4.10	0.024		0.8	7.14	386	1460	2.9	<2	2.73	<0.5	10	99	51	2.66
B292195		3.88	0.083		<0.5	7.15	192	1400	3.1	2	2.74	<0.5	9	100	52	2.55
B292196		1.82	<0.005		<0.5	0.15	<5	20	<0.5	<2	22.0	<0.5	1	10	2	0.13
B292197		4.86	0.111		0.6	7.46	248	1190	3.7	6	2.60	<0.5	12	88	53	2.73
B292198		7.08	0.123		1.1	6.30	764	500	3.8	11	1.76	1.3	8	74	20	1.51
B292199		6.16	0.643		1.5	8.00	432	1170	4.6	47	2.19	1.1	4	57	38	1.68
B292200		6.24	1.115		0.8	7.03	903	1180	4.5	27	2.19	0.5	7	60	101	1.73
B292201		3.60	0.430		1.1	7.03	760	1060	4.7	38	2.07	<0.5	8	60	62	1.53
B292202		2.98	0.248		1.2	6.75	361	970	4.3	26	2.11	0.5	4	68	85	1.64
B292203		5.42	0.061	0.062	<0.5	7.38	719	1270	4.7	3	1.85	<0.5	7	63	88	1.58
B292204		6.06	0.127	0.124	0.5	6.70	945	1310	4.6	14	1.64	<0.5	6	68	92	1.55
B292205		4.44	0.193	0.192	<0.5	6.71	407	1190	4.2	10	1.54	<0.5	6	74	114	1.86
B292206		5.96	0.138		1.3	6.46	599	1370	4.6	49	1.68	<0.5	8	75	96	1.60
B292207		6.66	0.565		<0.5	7.06	389	1330	3.9	41	1.68	<0.5	7	65	44	1.67
B292208		4.86	2.82		1.2	7.01	344	1510	2.9	242	1.74	<0.5	8	91	70	2.60
B292209		<0.02	3.00													
B292210		0.10	1.560		<0.5	6.42	1205	650	5.9	<2	0.01	<0.5	5	206	37	3.52
B292211		6.00	0.381		5.8	6.78	346	700	2.5	10	2.22	0.8	8	93	118	3.57
B292212		6.72	0.323		2.8	6.64	253	560	3.8	43	2.02	3.3	6	63	24	1.97
B292213		4.56	0.324		2.1	6.64	169	760	3.7	23	2.19	2.2	6	54	37	1.70
B292214		1.62	0.353		0.8	7.24	125	1730	3.2	40	2.03	<0.5	9	89	38	2.56

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05051469

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B292175		0.01	4.05	0.87	219	2	1.64	19	580	27	0.09	17	403	0.27	34	10
B292176		<0.01	0.03	12.05	172	<1	0.01	<1	510	<2	0.01	<5	110	0.01	3	<10
B292177		0.01	3.88	0.91	235	2	1.90	19	650	25	0.19	13	491	0.32	41	20
B292178		0.01	4.10	0.81	221	4	1.68	18	650	26	0.29	13	415	0.29	39	20
B292179		0.01	5.33	0.26	167	18	0.98	10	470	27	0.51	7	291	0.10	13	10
B292180		0.01	3.80	0.85	213	<1	1.50	18	640	25	0.19	6	461	0.30	41	20
B292181		0.01	4.14	0.36	174	<1	1.21	11	510	28	0.12	<5	351	0.10	14	10
B292182		0.01	5.06	0.21	143	1	1.08	1	510	23	0.08	5	306	0.07	8	<10
B292183		0.01	3.63	1.00	304	<1	1.64	12	630	22	0.20	<5	516	0.29	47	10
B292184		0.01	3.88	0.93	229	2	1.48	18	630	42	0.33	15	477	0.29	42	20
B292185		0.01	3.89	0.90	189	1	1.63	16	650	22	0.23	<5	464	0.31	40	30
B292186		0.01	3.70	0.84	211	2	1.61	19	630	21	0.28	<5	471	0.30	40	10
B292187		0.01	3.98	0.87	229	3	1.63	19	610	25	0.26	<5	500	0.30	41	40
B292188		0.01	3.44	0.85	266	2	1.58	19	660	21	0.22	<5	528	0.31	42	10
B292189																
B292190		0.01	1.62	1.26	400	1	2.80	49	640	16	0.58	<5	150	0.29	92	<10
B292191		0.01	3.89	0.87	296	12	1.69	20	660	21	0.19	10	552	0.31	43	50
B292192		0.01	3.64	0.95	307	3	1.91	21	710	17	0.15	<5	592	0.34	44	30
B292193		0.01	3.82	1.06	340	59	1.72	17	680	20	0.30	<5	581	0.32	47	30
B292194		0.01	4.12	1.11	355	17	1.64	19	700	22	0.25	<5	560	0.32	53	40
B292195		0.02	3.75	1.02	356	37	1.22	16	670	18	0.20	10	442	0.31	51	40
B292196		<0.01	0.04	12.25	156	<1	0.02	1	570	<2	0.01	<5	128	<0.01	2	<10
B292197		0.02	3.69	0.93	390	3	1.42	16	720	29	0.20	19	435	0.32	55	30
B292198		0.04	2.76	0.48	305	1	0.45	8	400	91	0.25	14	149	0.14	33	20
B292199		0.03	3.79	0.51	259	1	1.03	11	480	102	0.41	18	269	0.16	38	30
B292200		0.02	3.65	0.48	169	1	1.17	11	430	51	0.71	20	289	0.15	36	60
B292201		0.03	3.44	0.49	139	<1	1.20	12	430	46	0.47	12	287	0.15	36	100
B292202		0.02	3.38	0.55	184	<1	1.12	10	440	37	0.48	10	277	0.15	35	20
B292203		0.01	3.69	0.55	116	<1	1.57	10	470	19	0.41	5	349	0.16	37	10
B292204		0.01	3.63	0.52	114	<1	1.55	11	440	19	0.39	8	334	0.15	36	40
B292205		0.01	3.28	0.45	87	<1	1.53	13	410	15	0.92	8	315	0.14	33	10
B292206		0.01	3.64	0.50	94	1	1.73	10	440	24	0.45	5	356	0.16	37	30
B292207		0.01	3.40	0.54	140	2	1.64	11	430	13	0.32	5	334	0.14	35	30
B292208		0.01	3.97	0.84	336	13	1.02	14	650	81	0.34	30	382	0.25	47	20
B292209																
B292210		0.04	2.56	0.33	83	1	0.10	18	310	24	0.01	104	84	0.24	89	10
B292211		0.04	3.22	0.90	936	4	0.31	13	670	266	1.48	98	234	0.22	46	40
B292212		0.08	3.09	0.54	879	<1	0.04	8	420	284	0.36	37	126	0.13	33	20
B292213		0.06	3.49	0.48	536	<1	0.11	9	440	168	0.40	29	198	0.16	34	20
B292214		0.03	3.44	0.73	332	5	1.22	19	620	77	0.19	32	437	0.31	41	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05051469

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B292175		34
B292176		8
B292177		28
B292178		30
B292179		24
B292180		43
B292181		17
B292182		10
B292183		33
B292184		27
B292185		21
B292186		25
B292187		27
B292188		31
B292189		
B292190		187
B292191		35
B292192		43
B292193		38
B292194		42
B292195		37
B292196		10
B292197		44
B292198		201
B292199		137
B292200		58
B292201		37
B292202		85
B292203		44
B292204		32
B292205		21
B292206		18
B292207		24
B292208		59
B292209		
B292210		42
B292211		216
B292212		562
B292213		358
B292214		40

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 1-JUL-2005
Account: STRGOL

CERTIFICATE VA05052412

Project: Dublin Gulch-1735

P.O. No.:

This report is for 164 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 29-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER


SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3



This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292215		1.56	<0.005		<0.5	9.77	63	810	2.1	<2	0.19	<0.5	12	119	18	4.38
B292216		1.52	<0.005		<0.5	0.14	<5	20	<0.5	<2	20.4	<0.5	1	9	<1	0.14
B292217		5.70	<0.005		<0.5	11.40	70	1010	2.4	<2	0.36	<0.5	14	133	23	5.04
B292218		6.24	<0.005		<0.5	12.15	90	1020	2.8	<2	0.32	<0.5	15	129	24	5.10
B292219		4.52	<0.005		<0.5	10.80	119	930	2.4	<2	0.41	<0.5	14	126	20	4.75
B292220		3.92	<0.005		<0.5	12.10	112	970	2.5	<2	0.35	<0.5	14	143	20	5.17
B292221		1.62	<0.005		<0.5	12.20	134	1040	2.4	<2	0.40	<0.5	14	136	21	4.98
B292222		1.46	<0.005		<0.5	10.60	149	900	2.5	<2	0.50	<0.5	13	130	19	4.33
B292223		5.42	<0.005		<0.5	8.98	249	980	2.0	<2	0.93	<0.5	11	162	18	3.67
B292224		5.10	<0.005		<0.5	10.75	172	1190	2.5	<2	0.77	<0.5	14	148	36	4.41
B292225		5.94	<0.005		<0.5	10.10	82	990	2.0	<2	0.37	<0.5	12	149	23	3.78
B292226		6.22	<0.005		<0.5	8.63	58	900	1.7	2	0.28	<0.5	11	134	15	2.77
B292227		6.72	<0.005		<0.5	5.34	214	600	1.0	<2	0.33	<0.5	7	140	24	1.87
B292228		5.96	<0.005		<0.5	3.23	148	410	0.6	2	0.25	<0.5	3	142	10	1.33
B292229		0.04	<0.005													
B292230		0.10	1.405		<0.5	6.90	1125	640	4.9	<2	0.01	<0.5	5	194	40	3.51
B292231		6.38	0.005		<0.5	3.01	175	400	0.5	2	0.12	<0.5	6	113	7	1.04
B292232		4.64	<0.005		<0.5	3.29	129	350	0.5	<2	0.22	<0.5	4	118	6	1.01
B292233		6.02	<0.005		<0.5	6.08	108	700	1.2	2	0.27	<0.5	7	126	13	1.68
B292234		5.00	0.008		<0.5	4.45	192	470	0.9	<2	0.49	<0.5	7	123	14	1.57
B292235		4.62	0.050		<0.5	8.28	567	1510	2.6	7	1.56	<0.5	10	96	90	2.13
B292236		1.94	<0.005		<0.5	0.13	17	10	<0.5	<2	17.15	<0.5	<1	12	2	0.11
B292237		5.12	0.047		<0.5	7.69	852	1600	2.6	4	1.59	<0.5	9	106	90	2.04
B292238		5.66	0.173		<0.5	7.50	1660	1490	2.4	19	1.63	<0.5	11	99	57	2.02
B292239		5.64	0.159		<0.5	7.44	2730	1460	2.7	21	1.85	<0.5	12	98	84	2.17
B292240		3.28	0.083		<0.5	8.13	389	1570	2.7	10	1.77	<0.5	9	101	91	2.35
B292241		1.14	0.017		<0.5	7.85	315	1480	2.7	2	1.47	<0.5	10	94	99	2.12
B292242		1.06	0.016		<0.5	7.86	325	1470	2.7	8	1.43	<0.5	9	95	90	2.07
B292243		4.58	0.035		<0.5	7.81	781	1380	2.9	5	1.57	<0.5	9	101	43	1.97
B292244		1.32	0.018		<0.5	7.92	288	1790	3.4	2	2.61	<0.5	10	128	34	2.87
B292245		2.16	0.108		<0.5	7.26	1890	1620	2.7	13	1.60	<0.5	13	104	47	2.46
B292246		6.42	0.042		<0.5	7.50	327	1690	2.4	12	2.45	<0.5	7	86	66	2.66
B292247		6.78	0.058		<0.5	7.67	947	1300	2.6	9	1.27	<0.5	7	102	91	1.88
B292248		4.40	0.110		<0.5	7.79	2640	1630	2.5	20	1.38	<0.5	15	109	106	2.31
B292249		0.04	0.107													
B292250		0.10	3.04		0.6	7.15	6	2080	3.3	<2	4.96	<0.5	23	138	104	5.14
B292251		4.02	0.033		<0.5	7.90	711	1400	3.1	4	1.63	<0.5	8	117	98	2.09
B292252		4.96	0.057		<0.5	7.91	1575	1470	3.1	6	1.48	<0.5	9	99	91	2.37
B292253		4.32	0.142		<0.5	7.89	2950	1540	2.9	16	2.06	<0.5	24	100	92	2.53
B292254		0.60	0.168		<0.5	8.23	1475	1820	2.9	28	1.75	<0.5	14	102	95	2.27

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B292215		0.03	4.69	1.06	549	<1	1.26	39	400	50	0.01	<5	150	0.43	97	<10
B292216		0.01	0.03	11.55	166	<1	0.01	<1	520	<2	0.02	<5	112	0.01	3	<10
B292217		0.02	5.56	1.21	458	<1	1.40	42	640	25	0.01	9	153	0.50	103	<10
B292218		0.01	5.73	1.21	495	<1	1.32	41	630	21	<0.01	<5	176	0.52	110	10
B292219		0.01	5.18	1.10	561	<1	1.36	34	340	22	<0.01	<5	149	0.47	102	10
B292220		0.01	4.94	1.20	627	1	1.33	40	970	22	0.01	<5	185	0.51	106	<10
B292221		0.01	5.83	1.19	652	<1	1.34	38	950	21	<0.01	5	175	0.48	105	<10
B292222		0.01	5.49	1.04	507	<1	1.15	38	1650	17	<0.01	<5	160	0.48	106	<10
B292223		0.01	4.19	0.89	407	<1	0.83	32	350	11	<0.01	6	113	0.38	76	10
B292224		0.01	5.65	1.14	452	<1	0.67	37	390	20	<0.01	<5	146	0.48	97	<10
B292225		<0.01	5.04	1.03	361	3	0.80	33	210	15	0.02	<5	132	0.44	83	10
B292226		0.01	5.06	0.88	201	2	0.84	24	190	20	<0.01	<5	124	0.35	69	<10
B292227		<0.01	3.02	0.51	168	2	0.73	20	130	10	0.01	5	101	0.21	39	<10
B292228		0.01	1.72	0.24	128	2	0.56	12	90	7	0.01	<5	61	0.16	24	<10
B292229																
B292230		0.08	2.80	0.35	80	3	0.11	14	280	25	0.01	109	95	0.18	80	10
B292231		<0.01	1.69	0.21	94	1	0.66	13	70	8	0.01	<5	60	0.12	18	<10
B292232		0.02	1.94	0.20	100	1	0.70	11	110	13	<0.01	<5	60	0.11	17	<10
B292233		0.01	3.18	0.48	126	2	0.72	15	130	10	0.01	<5	98	0.23	44	<10
B292234		0.01	2.14	0.44	171	2	0.94	16	140	12	0.01	<5	129	0.18	29	10
B292235		0.01	4.17	0.96	95	2	1.71	18	590	15	0.02	<5	520	0.31	37	10
B292236		0.01	0.03	10.90	134	<1	0.01	<1	440	4	0.02	<5	123	<0.01	1	<10
B292237		0.01	4.20	0.91	104	2	1.44	19	590	15	0.04	<5	507	0.29	34	10
B292238		0.01	4.14	0.86	94	2	1.46	20	600	15	0.06	7	439	0.28	34	10
B292239		0.01	4.00	0.88	88	2	1.48	20	600	19	0.18	<5	483	0.29	35	20
B292240		0.01	4.34	0.96	119	3	1.72	22	710	14	0.02	<5	534	0.33	39	20
B292241		0.01	3.92	0.90	108	2	1.41	22	600	19	0.01	<5	443	0.31	35	10
B292242		0.01	3.89	0.90	108	2	1.40	19	570	19	0.01	<5	434	0.30	35	30
B292243		0.01	3.71	0.84	139	5	1.65	20	550	16	0.04	<5	487	0.30	36	10
B292244		0.01	3.35	0.91	258	1	1.53	24	750	19	0.01	<5	439	0.35	43	20
B292245		0.02	3.77	0.76	156	1	1.00	23	610	16	0.04	<5	288	0.29	35	20
B292246		0.01	4.43	0.88	226	2	1.28	23	690	15	0.02	<5	379	0.30	34	20
B292247		0.01	4.36	0.76	93	6	1.59	19	520	16	0.13	<5	452	0.27	33	10
B292248		0.01	4.73	0.76	83	4	1.34	19	570	10	0.21	<5	417	0.26	32	30
B292249																
B292250		0.01	3.49	3.04	1045	14	2.42	69	2430	29	0.31	<5	1735	0.37	161	<10
B292251		0.01	4.12	0.76	82	3	1.64	19	590	18	0.16	<5	480	0.28	34	10
B292252		0.01	3.97	0.82	115	2	1.53	21	600	15	0.09	<5	431	0.29	36	20
B292253		0.01	4.14	0.82	131	2	1.52	23	650	17	0.26	5	457	0.29	34	20
B292254		0.01	5.19	0.90	111	1	1.49	25	710	13	0.13	<5	484	0.34	43	40

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B292215		99
B292216		8
B292217		115
B292218		98
B292219		99
B292220		105
B292221		97
B292222		93
B292223		59
B292224		88
B292225		73
B292226		54
B292227		23
B292228		18
B292229		
B292230		42
B292231		13
B292232		14
B292233		31
B292234		38
B292235		13
B292236		14
B292237		12
B292238		13
B292239		11
B292240		16
B292241		15
B292242		14
B292243		24
B292244		41
B292245		26
B292246		24
B292247		15
B292248		11
B292249		
B292250		96
B292251		11
B292252		19
B292253		17
B292254		17

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292255		6.42	0.046		<0.5	8.09	822	1640	3.0	<2	1.72	<0.5	13	105	122	2.41
B292256		1.72	<0.005		<0.5	0.13	6	10	<0.5	<2	20.5	<0.5	<1	12	2	0.12
B292257		5.70	0.062		<0.5	8.08	836	1790	2.6	5	1.79	<0.5	11	106	108	2.37
B292258		5.06	0.086		<0.5	7.93	458	1600	2.7	13	1.64	<0.5	14	98	105	2.49
B292259		4.02	0.110		0.7	8.08	362	1660	2.9	10	2.08	<0.5	13	106	115	2.65
B292260		3.44	0.121		<0.5	8.05	435	1560	2.7	12	1.55	<0.5	10	94	152	2.79
B292261		2.70	0.268		<0.5	7.93	302	1660	2.9	18	1.98	<0.5	12	115	91	2.50
B292262		2.64	0.125		<0.5	7.91	287	1630	2.9	5	2.02	<0.5	10	93	96	2.45
B292263		6.36	0.110		<0.5	8.51	223	1650	3.2	17	2.29	<0.5	14	110	78	2.54
B292264		5.90	0.020		1.0	7.76	119	1480	3.1	<2	2.69	<0.5	9	91	68	2.30
B292265		6.36	0.151		<0.5	8.48	185	1690	3.1	11	2.29	<0.5	12	94	87	2.50
B292266		4.44	0.029		<0.5	8.10	134	1630	3.0	8	2.37	<0.5	10	85	65	2.43
B292267		5.68	0.060		0.5	8.33	1585	1600	3.1	4	1.78	<0.5	23	107	79	2.47
B292268		6.44	0.034		<0.5	7.97	1030	1600	3.0	<2	1.94	<0.5	11	101	78	2.47
B292269		0.04	0.035													
B292270		0.10	2.81		<0.5	7.88	2200	750	13.8	<2	0.02	<0.5	1	143	105	3.50
B292271		5.96	0.035		<0.5	7.90	154	1740	3.0	<2	2.06	<0.5	10	89	70	2.55
B292272		6.16	0.088		<0.5	7.67	152	1570	3.0	4	2.07	<0.5	8	98	56	2.42
B292273		6.22	0.016		<0.5	8.08	157	1720	3.1	<2	2.33	<0.5	9	110	42	2.51
B292274		5.62	0.053		0.6	7.23	525	1360	2.9	2	2.06	<0.5	14	87	74	2.26
B292275		1.32	0.116		0.7	7.69	148	1580	2.7	17	2.34	<0.5	11	86	96	2.38
B292276		1.84	<0.005		<0.5	0.14	9	20	<0.5	<2	21.5	<0.5	1	11	2	0.13
B292277		4.92	0.096		<0.5	7.80	833	1670	2.8	14	1.48	1.0	13	93	79	2.59
B292278		3.28	0.085		<0.5	7.75	666	1780	3.0	10	1.95	0.8	13	56	97	2.52
B292279		5.60	<0.005		<0.5	8.04	167	1690	3.2	<2	2.33	0.8	10	112	17	2.51
B292280		3.16	0.022		<0.5	8.20	356	1740	3.1	5	1.53	3.5	10	91	42	2.58
B292281		1.30	0.018		<0.5	7.38	336	1560	3.1	<2	1.73	2.9	10	83	76	2.66
B292282		1.18	0.023		<0.5	8.04	346	1700	3.3	<2	1.78	3.1	10	90	70	2.82
B292283		2.94	0.042		5.0	8.07	1110	810	3.0	5	0.23	7.5	2	147	99	3.63
B292284		2.42	0.126	0.114	0.9	8.40	251	1180	3.1	8	1.85	2.8	8	109	34	2.69
B292285		4.64	0.043		0.5	8.10	245	1660	3.1	8	2.27	<0.5	12	112	36	2.50
B292286		4.76	0.115	0.121	<0.5	7.53	365	1660	2.8	22	1.92	<0.5	12	94	71	2.43
B292287		1.16	0.015		<0.5	7.75	268	1440	3.3	<2	3.94	<0.5	21	92	20	4.22
B292288		3.46	0.040		<0.5	7.65	241	1520	3.1	2	2.04	<0.5	10	103	65	2.41
B292289		0.04	0.034	0.032												
B292290		0.10	4.61		9.5	7.98	25	500	0.9	<2	3.02	1.7	20	23	135	4.34
B292291		7.34	0.042		<0.5	7.43	179	1560	2.8	6	2.04	<0.5	9	106	44	2.24
B292292		4.00	0.036		<0.5	7.78	90	1530	3.0	2	2.54	<0.5	8	97	28	2.30
B292293		2.58	0.278		6.0	7.52	539	1520	3.1	6	2.45	0.9	13	61	115	2.56
B292294		2.46	0.068		0.7	7.26	979	1580	3.2	5	1.89	0.8	11	55	79	2.45

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B292255		0.01	4.26	0.84	129	5	1.56	19	640	15	0.08	<5	465	0.32	41	40
B292256		<0.01	0.03	11.50	157	<1	0.01	1	520	4	0.01	<5	108	<0.01	2	<10
B292257		0.01	4.72	0.85	143	2	1.43	21	650	20	0.04	5	436	0.31	39	40
B292258		0.01	4.52	0.77	157	2	1.41	22	640	18	0.08	<5	388	0.30	37	30
B292259		0.01	4.44	0.79	157	2	1.58	21	650	21	0.17	<5	477	0.31	39	30
B292260		0.01	4.65	0.77	147	3	1.38	20	620	20	0.03	7	389	0.29	36	40
B292261		0.01	4.12	0.78	158	3	1.52	20	630	15	0.17	<5	458	0.31	38	20
B292262		0.01	4.10	0.78	165	3	1.55	22	660	17	0.13	<5	465	0.32	39	10
B292263		0.01	3.92	0.81	197	3	1.74	21	670	20	0.12	<5	500	0.31	38	20
B292264		0.01	3.92	0.77	210	3	1.58	16	630	30	0.12	<5	509	0.30	37	10
B292265		0.01	4.43	0.83	164	2	1.63	23	670	25	0.21	<5	469	0.31	39	20
B292266		0.01	4.04	0.81	187	3	1.66	21	660	23	0.14	<5	468	0.32	40	20
B292267		0.01	4.09	0.81	144	1	1.63	22	640	21	0.21	5	464	0.31	39	10
B292268		0.01	3.95	0.82	172	3	1.56	20	670	23	0.14	<5	438	0.32	39	20
B292269																
B292270		0.11	3.22	0.40	72	3	0.09	7	320	33	0.02	169	149	0.29	109	20
B292271		0.01	4.40	0.81	223	5	1.53	17	670	18	0.08	<5	434	0.32	39	20
B292272		0.01	3.46	0.81	186	3	1.53	21	630	19	0.08	6	413	0.30	38	20
B292273		0.02	4.03	0.85	247	3	1.58	20	660	22	0.02	8	442	0.32	40	30
B292274		0.02	3.92	0.70	204	4	1.32	21	560	26	0.07	5	356	0.27	33	30
B292275		0.01	4.51	0.77	169	3	1.37	21	600	20	0.30	<5	389	0.28	35	30
B292276		0.01	0.04	12.05	182	<1	0.02	2	500	3	<0.01	<5	112	<0.01	2	<10
B292277		0.01	4.33	0.79	179	4	1.29	19	670	18	0.03	7	331	0.31	40	20
B292278		0.02	3.97	0.82	215	4	1.05	23	650	78	0.03	20	338	0.32	39	20
B292279		0.01	3.90	0.82	302	1	1.63	22	660	25	0.02	7	432	0.32	40	10
B292280		0.01	4.00	0.79	256	2	1.44	18	690	32	0.04	22	369	0.31	40	20
B292281		0.01	3.80	0.88	271	1	1.42	22	660	21	0.01	18	366	0.29	37	<10
B292282		0.01	3.95	0.97	277	3	1.50	20	690	24	0.01	10	392	0.32	40	10
B292283		0.33	3.66	0.49	71	7	0.15	7	460	1660	0.11	258	156	0.24	38	20
B292284		0.02	3.50	0.71	380	3	1.05	24	640	102	0.04	28	293	0.31	39	<10
B292285		0.01	3.79	0.82	255	3	1.73	22	640	21	0.05	10	552	0.31	39	10
B292286		0.01	3.80	0.89	231	2	1.38	21	610	23	0.01	12	449	0.30	38	10
B292287		0.01	3.71	1.62	643	2	1.69	27	820	21	0.02	7	598	0.41	82	20
B292288		0.01	3.60	0.85	225	3	1.54	18	610	13	0.02	13	452	0.30	37	10
B292289																
B292290		0.04	2.41	1.41	1040	14	1.76	14	950	29	0.71	<5	439	0.40	158	<10
B292291		0.02	3.86	0.80	220	4	1.55	20	580	16	0.01	9	423	0.28	34	10
B292292		0.02	3.68	0.85	285	4	1.63	22	620	21	0.01	12	419	0.29	35	10
B292293		0.06	3.66	0.94	296	9	0.97	20	610	239	0.13	37	317	0.29	37	10
B292294		0.02	3.79	0.81	242	7	1.11	18	610	26	0.02	21	327	0.30	37	20

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B292255		16
B292256		8
B292257		16
B292258		21
B292259		21
B292260		22
B292261		21
B292262		21
B292263		23
B292264		38
B292265		25
B292266		28
B292267		22
B292268		60
B292269		
B292270		18
B292271		31
B292272		25
B292273		37
B292274		38
B292275		31
B292276		8
B292277		97
B292278		134
B292279		77
B292280		464
B292281		833
B292282		798
B292283		342
B292284		703
B292285		61
B292286		30
B292287		71
B292288		20
B292289		
B292290		106
B292291		22
B292292		31
B292293		208
B292294		121

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292295		4.48	0.025		<0.5	7.35	135	1460	3.0	<2	1.72	<0.5	8	106	52	2.21
B292296		1.34	<0.005		<0.5	0.14	8	20	<0.5	<2	21.4	<0.5	1	12	2	0.14
B292297		5.88	0.034		<0.5	7.93	277	1620	3.1	<2	2.24	<0.5	9	117	44	2.43
B292298		6.20	0.023		<0.5	7.90	162	1480	3.1	<2	2.19	<0.5	9	99	50	2.32
B292299		1.96	0.029		<0.5	7.89	244	1520	3.2	<2	2.10	<0.5	9	99	72	2.39
B292300		5.94	0.074		<0.5	8.21	266	1640	3.2	3	2.18	<0.5	8	109	68	2.51
B292301		2.64	0.105		0.6	7.86	652	1620	3.1	5	1.95	<0.5	13	114	94	2.52
B292302		2.68	0.104		0.7	7.16	1650	1560	2.9	14	1.71	1.0	15	106	133	2.66
B292303		5.44	0.086		5.9	7.49	1240	610	2.9	8	1.60	3.9	7	125	89	2.33
B292304		3.50	0.022		<0.5	7.58	218	1420	2.9	<2	2.08	0.6	8	95	52	2.14
B292305		3.80	0.036		<0.5	7.70	262	1400	3.1	11	1.70	<0.5	11	122	56	2.19
B292306		3.24	0.026	0.019	<0.5	7.80	73	1560	3.1	<2	2.57	<0.5	8	98	44	2.49
B292307		5.24	0.267		<0.5	7.67	152	1420	3.2	9	2.06	<0.5	8	117	60	2.41
B292308		5.84	0.118		1.9	7.51	781	560	2.7	6	1.78	2.3	6	118	55	2.02
B292309		0.06	0.115													
B292310		0.10	2.80		<0.5	7.50	2140	730	12.1	<2	0.01	<0.5	2	152	108	3.42
B292311		4.84	0.142		4.0	7.05	1420	650	2.6	5	2.56	6.8	9	125	133	3.74
B292312		4.42	1.520		<0.5	6.85	295	1440	2.7	134	2.09	<0.5	14	115	154	2.63
B292313		6.04	0.277		0.7	7.25	191	1310	2.9	131	2.24	<0.5	10	118	77	2.29
B292314		6.20	0.290		<0.5	7.54	189	1520	3.2	9	2.51	<0.5	10	107	105	2.31
B292315		2.96	0.019		<0.5	8.00	185	1530	3.0	<2	2.62	<0.5	10	28	60	2.49
B292316		1.80	<0.005		<0.5	0.13	<5	20	<0.5	<2	22.8	<0.5	1	2	2	0.11
B292317		3.08	0.181		0.8	7.01	372	1480	2.7	11	1.99	<0.5	10	24	110	2.23
B292318		5.32	0.044		<0.5	7.75	304	1590	3.1	<2	2.56	<0.5	11	27	85	2.38
B292319		2.08	0.077		0.6	7.39	358	1580	2.8	12	1.97	<0.5	10	26	141	2.35
B292320		5.12	0.026		<0.5	7.56	657	1480	2.9	3	2.32	<0.5	11	29	64	2.33
B292321		2.32	0.029		0.9	7.99	253	1640	3.1	<2	2.61	<0.5	11	28	77	2.50
B292322		2.22	<0.005		<0.5	6.33	25	460	0.7	<2	3.02	<0.5	13	64	27	3.47
B292323		5.82	0.021		<0.5	7.21	302	1540	2.9	<2	2.33	<0.5	11	28	53	2.32
B292324		5.40	0.040		<0.5	7.79	474	1600	3.1	3	2.37	<0.5	10	29	45	2.48
B292325		5.02	0.063		0.9	7.83	385	1610	2.8	4	2.26	1.2	10	29	117	2.92
B292326		3.66	0.053		<0.5	7.28	577	1600	3.0	<2	2.31	<0.5	11	30	136	2.60
B292327		5.10	0.095		<0.5	7.25	780	1290	1.9	9	1.46	<0.5	12	24	124	2.37
B292328		4.96	0.043		0.6	8.31	530	1610	3.2	6	2.47	<0.5	10	29	67	2.62
B292329		0.04	0.055													
B292330		0.12	0.872		2.3	8.08	30	470	0.8	<2	2.03	0.9	25	106	2140	5.33
B292331		2.80	0.060		<0.5	7.96	71	1630	3.1	22	2.41	<0.5	10	31	55	2.59
B292332		1.96	0.031		<0.5	7.55	269	1640	3.0	<2	2.08	<0.5	10	29	68	2.60
B292333		6.26	0.689		<0.5	7.64	162	1550	3.3	96	2.44	<0.5	10	30	37	2.47
B292334		6.60	0.121		<0.5	7.93	236	1550	3.2	4	2.65	<0.5	9	31	51	2.42

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method Analyte Units LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B292295		0.01	3.83	0.72	228	3	1.41	15	540	31	0.02	5	351	0.26	33	10
B292296		<0.01	0.04	11.90	165	<1	0.02	<1	510	4	0.01	<5	112	<0.01	2	<10
B292297		0.01	3.81	0.78	282	2	1.52	21	640	23	0.04	<5	414	0.30	37	20
B292298		0.01	3.81	0.75	244	2	1.62	17	600	22	0.02	10	438	0.28	34	10
B292299		0.01	3.76	0.78	237	4	1.76	19	630	15	0.10	<5	472	0.31	37	<10
B292300		0.01	3.90	0.83	286	5	1.66	26	640	18	0.06	<5	494	0.31	38	10
B292301		0.01	3.94	0.79	297	13	1.54	23	630	19	0.11	6	417	0.30	36	10
B292302		0.01	4.02	0.75	262	18	1.38	25	600	16	0.19	7	374	0.29	35	10
B292303		0.10	3.13	0.46	415	11	0.12	10	540	405	0.14	30	70	0.22	30	30
B292304		0.01	3.74	0.68	268	6	1.43	16	560	27	0.01	<5	361	0.27	33	10
B292305		0.01	3.79	0.66	201	7	1.58	18	540	22	0.09	<5	400	0.25	31	10
B292306		0.01	3.50	0.76	328	2	1.63	25	630	24	0.06	<5	446	0.31	37	<10
B292307		0.01	3.72	0.74	267	8	1.58	21	580	29	0.18	7	421	0.29	34	20
B292308		0.06	3.24	0.32	438	3	0.04	15	590	257	0.53	25	42	0.23	32	30
B292309																
B292310		0.10	3.21	0.38	70	3	0.09	11	330	32	0.02	162	144	0.19	102	10
B292311		0.16	3.01	0.45	722	4	0.16	17	560	748	1.83	36	97	0.22	31	30
B292312		0.01	3.84	0.67	228	18	1.46	21	570	23	0.67	<5	410	0.27	33	40
B292313		0.02	3.70	0.64	205	7	1.46	22	530	17	0.53	6	390	0.26	31	30
B292314		0.01	3.81	0.76	176	7	1.73	16	590	18	0.36	<5	499	0.30	36	<10
B292315		0.01	3.66	0.82	216	7	1.77	23	630	22	0.21	<5	488	0.31	37	<10
B292316		<0.01	0.04	12.75	172	<1	0.01	<1	580	2	<0.01	<5	122	<0.01	1	<10
B292317		0.01	3.64	0.72	169	7	1.52	19	580	18	0.23	5	418	0.28	34	10
B292318		0.01	3.76	0.79	207	4	1.69	22	630	19	0.20	<5	474	0.32	37	30
B292319		0.01	4.02	0.76	159	16	1.49	21	620	26	0.28	<5	415	0.30	36	10
B292320		0.01	3.53	0.74	202	1	1.59	20	610	21	0.30	<5	473	0.30	36	<10
B292321		<0.01	3.93	0.80	214	7	1.72	19	670	18	0.34	<5	548	0.32	38	<10
B292322		0.01	0.88	1.48	689	1	2.01	35	560	7	0.12	<5	271	0.32	111	<10
B292323		0.01	3.76	0.74	211	1	1.67	17	610	18	0.20	<5	483	0.30	36	<10
B292324		<0.01	3.74	0.83	241	7	1.71	22	620	21	0.20	<5	538	0.31	37	<10
B292325		0.03	4.02	0.83	210	6	1.52	21	680	24	0.71	7	464	0.30	36	80
B292326		<0.01	4.07	0.92	205	3	1.66	16	630	16	0.36	6	485	0.31	39	10
B292327		0.01	4.97	0.64	130	8	0.97	11	570	20	0.69	11	277	0.23	29	40
B292328		0.03	3.93	0.88	241	3	1.68	21	700	21	0.30	<5	474	0.34	41	<10
B292329																
B292330		0.03	1.80	1.41	464	3	3.21	54	670	22	0.65	<5	214	0.31	96	<10
B292331		0.01	3.98	0.84	272	11	1.69	21	660	27	0.24	<5	480	0.31	38	<10
B292332		0.01	3.73	0.89	272	7	1.83	20	660	25	0.23	<5	451	0.32	40	10
B292333		0.01	3.75	0.80	308	4	1.75	20	620	34	0.16	5	467	0.31	38	<10
B292334		0.01	3.72	0.81	257	5	1.75	17	650	31	0.21	<5	485	0.31	38	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B292295		43
B292296		8
B292297		39
B292298		40
B292299		29
B292300		35
B292301		134
B292302		167
B292303		586
B292304		158
B292305		33
B292306		48
B292307		59
B292308		460
B292309		
B292310		17
B292311		880
B292312		26
B292313		22
B292314		19
B292315		24
B292316		9
B292317		23
B292318		28
B292319		25
B292320		27
B292321		26
B292322		56
B292323		27
B292324		34
B292325		202
B292326		22
B292327		24
B292328		44
B292329		
B292330		214
B292331		54
B292332		57
B292333		67
B292334		44

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292335		6.16	0.067		<0.5	7.93	238	1600	3.1	<2	2.62	<0.5	10	30	49	2.52
B292336		1.30	<0.005		<0.5	0.12	11	20	<0.5	<2	21.2	<0.5	1	2	1	0.11
B292337		6.46	0.409		<0.5	7.19	93	1540	3.0	17	2.59	<0.5	8	28	42	2.37
B292338		5.84	<0.005		<0.5	6.94	30	480	0.7	<2	3.17	<0.5	14	67	32	3.77
B292339		5.90	0.012		<0.5	7.66	137	1560	3.1	<2	2.63	<0.5	10	30	45	2.41
B292340		5.96	0.070		<0.5	7.52	63	1620	3.1	9	2.60	<0.5	11	32	54	2.52
B292341		2.90	0.224		<0.5	7.68	127	1660	3.0	11	2.60	<0.5	11	29	53	2.67
B292342		3.22	0.077		<0.5	8.08	201	1690	3.1	11	2.50	<0.5	12	31	55	2.72
B292343		6.48	0.014		<0.5	7.35	349	1580	3.2	<2	2.75	<0.5	9	30	28	2.47
B292344		5.94	0.048		<0.5	7.77	104	1470	3.4	<2	2.40	<0.5	10	26	43	2.33
B292345		6.60	0.037		<0.5	7.39	87	1480	3.1	2	2.44	<0.5	8	26	54	2.31
B292346		5.84	0.209		0.5	7.74	358	1470	3.2	17	2.51	<0.5	11	27	60	2.44
B292347		4.60	0.026		<0.5	7.04	25	1480	2.9	2	2.59	<0.5	8	26	34	2.29
B292348		7.26	0.017		<0.5	6.86	129	1400	3.0	<2	2.24	<0.5	10	29	42	2.25
B292349		0.04	0.029													
B292350		0.10	1.405		<0.5	7.33	1295	740	6.0	<2	0.01	<0.5	5	221	41	3.97
B292351		5.78	0.035		<0.5	7.09	483	1500	3.0	<2	2.29	<0.5	9	30	57	2.36
B292352		6.94	0.033		0.7	7.03	193	1570	3.1	3	2.73	<0.5	14	31	72	2.53
B292353		5.72	0.071		0.5	7.01	229	1530	3.3	<2	2.26	<0.5	15	35	101	2.48
B292354		5.54	0.242		0.6	7.55	408	1580	3.1	38	2.53	<0.5	11	32	62	2.58
B292355		6.36	0.036		<0.5	8.05	81	1660	3.3	4	2.76	<0.5	10	32	54	2.64
B292356		2.38	<0.005		<0.5	0.16	5	20	<0.5	<2	21.2	<0.5	<1	2	2	0.13
B292357		5.20	1.445		<0.5	7.73	325	1610	3.2	82	2.56	<0.5	8	31	46	2.50
B292358		5.94	0.084		<0.5	7.83	117	1540	3.3	6	3.38	<0.5	8	27	51	2.41
B292359		6.86	0.022		<0.5	7.24	179	1480	3.3	<2	2.31	<0.5	9	29	34	2.34
B292360		6.62	0.023		0.6	7.13	118	1440	3.0	7	2.32	<0.5	8	28	60	2.28
B292361		3.38	0.020		<0.5	7.31	379	1560	3.1	2	2.28	<0.5	8	28	48	2.37
B292362		2.74	0.018		<0.5	7.48	430	1480	3.1	<2	2.22	<0.5	8	28	43	2.36
B292363		6.78	0.041		0.6	7.46	87	1500	3.0	6	2.28	<0.5	9	28	63	2.33
B292364		6.02	0.020		<0.5	7.71	278	1540	3.2	<2	2.41	<0.5	10	29	55	2.44
B292365		6.82	0.100		<0.5	7.14	103	1530	3.1	<2	2.47	<0.5	9	28	44	2.32
B292366		3.46	0.068		0.7	7.16	629	1300	2.8	9	2.35	<0.5	10	28	52	2.59
B292367		3.04	0.023		<0.5	6.82	89	1520	2.8	<2	1.86	<0.5	10	30	52	2.29
B292368		6.42	0.053		<0.5	6.75	103	1410	2.9	6	2.33	<0.5	9	30	69	2.31
B292369		0.04	0.131													
B292370		0.10	0.433		2.5	8.04	5	1010	1.1	<2	1.37	<0.5	8	10	6960	3.09
B292371		5.88	0.192		<0.5	7.14	115	1600	2.5	18	2.04	<0.5	14	36	184	2.84
B292372		6.20	0.014		<0.5	6.97	127	1460	3.0	<2	2.41	<0.5	8	29	36	2.27
B292373		5.70	0.128		<0.5	7.41	51	1490	2.9	7	2.34	<0.5	9	32	66	2.38
B292374		6.22	0.020		<0.5	7.48	110	1490	3.2	3	2.50	<0.5	9	30	45	2.36

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B292335		0.01	3.58	0.85	276	4	1.76	19	670	27	0.21	<5	489	0.32	39	10
B292336		<0.01	0.03	11.65	163	<1	0.02	<1	440	2	<0.01	<5	114	<0.01	2	<10
B292337		0.01	3.60	0.81	282	4	1.75	18	600	30	0.18	<5	457	0.31	37	<10
B292338		0.01	0.92	1.61	742	1	2.15	36	590	9	0.17	<5	290	0.34	119	<10
B292339		<0.01	3.69	0.82	281	4	1.78	19	630	28	0.18	<5	512	0.31	38	10
B292340		<0.01	3.87	0.82	280	1	1.73	22	660	28	0.21	<5	506	0.32	40	<10
B292341		0.01	4.13	0.84	277	4	1.67	20	660	25	0.30	<5	501	0.32	40	10
B292342		<0.01	4.14	0.87	268	3	1.71	23	680	28	0.32	<5	506	0.33	40	10
B292343		0.01	3.53	0.83	316	2	1.84	24	650	22	0.13	<5	493	0.32	39	<10
B292344		0.01	3.80	0.76	256	3	1.78	16	590	25	0.17	6	447	0.29	35	10
B292345		0.03	3.81	0.76	248	7	1.77	19	600	25	0.17	<5	437	0.30	36	20
B292346		0.02	3.84	0.77	272	4	1.70	22	590	28	0.22	<5	458	0.29	36	10
B292347		0.01	3.72	0.73	280	2	1.73	18	610	29	0.12	<5	462	0.29	36	10
B292348		0.02	3.46	0.74	247	3	1.72	20	590	24	0.15	<5	436	0.29	36	10
B292349																
B292350		0.08	2.75	0.37	96	3	0.11	18	320	29	0.02	126	99	0.23	91	10
B292351		0.01	3.64	0.77	223	1	1.77	22	630	21	0.21	<5	471	0.31	38	20
B292352		0.01	3.78	0.76	258	3	1.78	24	640	22	0.27	<5	499	0.32	40	10
B292353		0.01	4.53	0.81	195	3	1.74	24	640	20	0.28	<5	456	0.36	45	150
B292354		0.01	3.77	0.85	232	1	1.79	22	660	23	0.34	<5	504	0.32	38	20
B292355		0.01	3.75	0.88	269	5	1.93	25	680	24	0.21	<5	530	0.33	40	10
B292356		<0.01	0.04	11.80	160	<1	0.02	3	540	<2	0.01	<5	116	<0.01	2	<10
B292357		0.01	3.66	0.85	258	2	1.85	22	660	38	0.21	5	487	0.31	40	10
B292358		0.01	3.69	0.81	279	5	1.72	21	630	25	0.24	<5	491	0.31	37	<10
B292359		0.01	3.51	0.76	277	1	1.71	20	620	27	0.15	<5	450	0.31	36	<10
B292360		0.01	4.07	0.74	246	2	1.72	20	570	37	0.19	<5	423	0.29	37	20
B292361		0.01	3.74	0.79	240	1	1.81	22	630	22	0.21	<5	458	0.31	38	10
B292362		0.01	3.62	0.79	232	2	1.80	18	630	20	0.20	<5	457	0.31	38	10
B292363		0.01	3.90	0.78	204	2	1.69	19	600	20	0.24	<5	471	0.30	36	20
B292364		0.01	3.56	0.81	244	3	1.74	18	630	28	0.21	5	475	0.31	38	10
B292365		0.01	3.63	0.77	280	2	1.70	21	620	25	0.19	<5	460	0.31	37	10
B292366		0.04	3.59	0.65	355	3	1.25	22	600	57	0.63	17	305	0.29	37	20
B292367		0.01	3.69	0.82	267	5	1.49	20	580	24	0.16	9	396	0.30	36	20
B292368		0.01	3.54	0.72	234	2	1.60	22	590	23	0.27	<5	451	0.30	35	40
B292369																
B292370		0.04	3.59	1.07	458	3	3.27	11	1860	6	0.22	<5	644	0.33	167	<10
B292371		0.01	5.18	0.80	201	11	1.46	21	650	18	0.64	<5	451	0.31	40	10
B292372		0.01	3.59	0.72	277	3	1.71	18	610	30	0.15	<5	471	0.30	35	<10
B292373		0.01	3.81	0.74	229	3	1.61	20	620	28	0.23	<5	462	0.30	35	20
B292374		0.01	3.64	0.77	269	6	1.75	21	640	25	0.20	<5	496	0.31	36	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B292335		48
B292336		8
B292337		47
B292338		70
B292339		48
B292340		51
B292341		45
B292342		44
B292343		50
B292344		45
B292345		36
B292346		54
B292347		54
B292348		49
B292349		
B292350		47
B292351		36
B292352		37
B292353		30
B292354		31
B292355		35
B292356		9
B292357		35
B292358		32
B292359		48
B292360		46
B292361		31
B292362		32
B292363		26
B292364		38
B292365		41
B292366		77
B292367		51
B292368		38
B292369		
B292370		54
B292371		29
B292372		55
B292373		41
B292374		47

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B292375		6.06	0.065		<0.5	6.69	151	1450	3.1	4	2.45	<0.5	7	28	50	2.25
B292376		1.54	<0.005		<0.5	0.15	<5	20	<0.5	<2	18.50	<0.5	<1	3	2	0.13
B292377		5.80	0.048		<0.5	7.00	455	1440	3.3	5	2.37	<0.5	8	30	45	2.32
B292378		5.90	0.075		<0.5	7.04	1240	1390	3.2	7	2.27	<0.5	19	30	53	2.25

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B292375		0.01	3.47	0.73	266	1	1.67	21	610	26	0.19	<5	459	0.31	36	10
B292376		<0.01	0.04	10.75	150	<1	0.01	5	510	<2	0.02	<5	102	0.01	3	<10
B292377		0.01	3.41	0.74	251	2	1.67	23	630	20	0.23	<5	474	0.30	35	10
B292378		0.01	3.72	0.70	212	7	1.68	19	600	20	0.37	<5	487	0.29	34	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052412

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B292375		52
B292376		7
B292377		42
B292378		30

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 1-JUL-2005
Account: STRGOL

CERTIFICATE VA05052041

Project: Dublin Gulch-1735

P.O. No.:

This report is for 56 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 29-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052041

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292924		4.48	0.010	<0.5	6.61	265	610	1.9	<2	0.60	<0.5	9	51	56	3.26	0.15
B292925		3.42	1.655	1.8	8.11	3170	890	2.5	24	0.68	<0.5	17	61	144	5.21	0.13
B292926		2.10	0.109	4.4	4.32	731	320	1.3	<2	0.76	36.8	5	24	97	5.53	0.89
B292927		3.24	0.011	0.9	6.68	311	610	1.8	<2	0.65	2.3	7	45	41	2.79	0.08
B292928		5.68	0.013	2.0	6.38	129	570	1.7	<2	0.79	1.6	8	46	33	3.23	0.07
B292929		0.04	0.017													
B292930		0.10	0.879	2.2	7.55	<5	440	0.7	<2	1.89	<0.5	22	100	1990	5.19	0.02
B292931		5.24	0.014	<0.5	7.02	324	620	2.0	<2	0.46	<0.5	10	51	37	3.01	0.06
B292932		0.74	0.846	18.1	5.57	2090	230	1.6	104	0.39	0.7	13	38	2050	6.20	0.13
B292933		4.90	0.015	0.9	6.77	238	480	2.0	<2	0.66	<0.5	12	50	47	3.34	0.06
B292934		5.00	0.009	<0.5	5.06	715	320	1.3	<2	0.74	<0.5	8	37	24	2.15	0.05
B292935		3.26	<0.005	<0.5	8.98	126	870	2.4	<2	0.34	<0.5	16	71	47	3.56	0.05
B292936		2.04	<0.005	<0.5	0.12	<5	20	<0.5	<2	19.85	<0.5	1	2	17	0.12	<0.01
B292937		2.80	0.009	<0.5	6.75	736	670	1.7	<2	0.89	<0.5	10	45	31	2.80	0.12
B292938		7.52	0.009	<0.5	7.95	165	830	2.3	<2	0.57	<0.5	12	65	46	3.59	0.12
B292939		2.26	0.023	6.1	7.37	136	580	2.0	<2	1.52	25.9	7	48	49	5.13	0.48
B292940		3.06	0.008	<0.5	3.12	58	210	0.7	3	0.34	<0.5	5	29	17	1.37	0.05
B292941		1.34	<0.005	5.4	2.70	22	180	0.6	<2	0.42	<0.5	6	22	17	1.48	0.03
B292942		1.50	<0.005	<0.5	2.88	24	190	0.6	<2	0.36	<0.5	6	26	11	1.38	0.03
B292943		6.14	0.017	<0.5	8.06	625	870	2.4	<2	0.64	<0.5	18	68	69	3.83	0.04
B292944		5.90	0.016	<0.5	9.06	575	960	2.8	<2	0.46	<0.5	20	78	128	4.61	0.07
B292945		3.30	0.042	1.0	4.24	2930	240	1.1	<2	0.82	2.7	7	28	23	2.47	0.06
B292946		5.82	0.019	1.7	7.93	794	680	2.2	<2	0.71	5.4	9	59	54	3.50	0.13
B292947		5.66	0.026	2.4	7.42	672	750	2.1	<2	0.59	3.5	8	53	66	2.52	0.09
B292948		6.22	0.007	<0.5	6.41	157	560	1.5	<2	0.86	<0.5	8	46	29	2.73	0.04
B292949		0.04	0.008													
B292950		0.10	0.091	<0.5	7.27	114	600	2.6	<2	0.55	<0.5	60	1235	412	9.05	0.04
B292951		6.34	0.016	1.0	7.60	998	580	1.8	<2	0.79	2.1	11	51	37	3.37	0.09
B292952		1.42	0.005	<0.5	8.14	49	1140	2.2	<2	0.96	<0.5	12	75	30	5.18	0.10
B292953		4.90	0.005	<0.5	8.84	195	1000	2.0	<2	0.49	<0.5	12	70	32	4.13	0.02
B292954		3.04	<0.005	<0.5	8.37	62	760	2.5	<2	0.44	<0.5	12	65	45	3.80	0.01
B292955		3.76	<0.005	<0.5	6.77	392	570	1.6	<2	0.62	<0.5	10	53	38	2.88	0.01
B292956		1.60	<0.005	<0.5	0.12	<5	10	<0.5	<2	20.1	<0.5	<1	2	1	0.11	<0.01
B292957		5.18	<0.005	<0.5	5.65	148	420	1.4	<2	0.96	<0.5	8	44	25	2.74	0.02
B292958		6.04	0.028	0.7	8.01	693	790	2.1	<2	0.86	1.9	11	66	57	3.33	0.07
B292959		4.08	0.933	2.9	7.47	3940	600	2.0	<2	0.96	11.2	11	55	72	3.81	0.22
B292960		3.36	0.025	1.5	6.73	174	790	1.7	<2	0.85	3.2	6	50	46	3.64	0.10
B292961		2.42	0.094	1.0	6.89	3160	660	1.8	3	0.42	<0.5	8	54	198	3.88	0.07
B292962		2.66	0.082	1.1	6.15	1820	510	1.5	13	0.50	<0.5	7	46	178	3.76	0.07
B292963		6.06	0.011	<0.5	4.18	208	310	1.2	<2	0.55	1.3	4	29	24	1.81	0.06

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052041

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292924		2.93	0.82	328	<1	0.09	22	340	20	0.69	10	85	0.21	61	20	61
B292925		4.33	1.15	349	1	0.13	40	480	99	2.22	20	97	0.21	97	10	53
B292926		1.94	0.62	957	1	0.03	15	200	1245	4.00	31	61	0.12	34	<10	4700
B292927		2.97	0.72	620	<1	0.14	24	290	121	0.93	14	63	0.24	61	10	390
B292928		2.90	0.81	609	1	0.07	23	270	475	0.83	16	66	0.22	60	10	278
B292929																
B292930		1.74	1.38	424	3	3.39	49	660	15	0.61	<5	203	0.30	91	<10	203
B292931		3.13	0.77	280	1	0.07	29	260	23	0.45	17	84	0.26	73	10	104
B292932		2.62	0.69	304	4	0.06	30	350	1695	4.81	662	27	0.15	55	10	154
B292933		3.08	0.82	452	2	0.08	28	310	29	1.16	23	234	0.25	69	20	65
B292934		2.06	0.56	503	<1	0.05	21	210	39	0.57	16	138	0.19	49	10	90
B292935		3.91	1.05	225	1	0.19	39	300	13	0.26	24	113	0.35	106	20	76
B292936		0.04	12.10	145	<1	0.02	3	500	<2	0.01	<5	109	0.01	3	<10	7
B292937		2.78	0.78	323	2	0.11	27	240	56	0.31	21	116	0.24	63	20	123
B292938		3.92	1.00	312	1	0.31	34	300	57	0.61	15	108	0.24	91	10	110
B292939		3.35	1.14	1955	1	0.07	26	280	1650	2.15	16	58	0.24	78	<10	3410
B292940		1.17	0.30	207	<1	0.04	11	160	11	0.08	5	58	0.13	25	20	26
B292941		1.10	0.33	197	<1	0.07	13	160	25	0.09	5	55	0.13	20	10	60
B292942		1.03	0.30	178	<1	0.05	10	160	9	0.06	7	53	0.13	23	10	25
B292943		4.20	1.13	260	3	0.74	45	330	17	0.69	18	134	0.26	98	10	55
B292944		4.80	1.18	225	3	0.70	52	330	20	1.38	24	127	0.28	118	10	59
B292945		1.83	0.61	494	<1	0.04	17	190	212	0.71	11	46	0.17	33	10	368
B292946		3.61	0.88	971	2	0.09	34	320	340	1.02	34	96	0.26	89	10	822
B292947		3.33	0.66	735	<1	0.07	30	270	390	0.92	44	68	0.28	82	10	537
B292948		2.50	0.79	373	<1	0.09	24	260	36	0.19	13	100	0.24	64	10	63
B292949																
B292950		2.33	0.64	394	9	0.14	501	360	151	0.02	11	51	0.25	97	30	623
B292951		3.14	0.83	1465	1	0.17	34	260	245	0.77	53	75	0.27	78	10	449
B292952		3.03	1.74	409	1	0.52	40	300	59	0.40	38	108	0.37	104	20	124
B292953		3.60	1.56	303	1	1.48	42	300	20	0.39	8	146	0.36	100	10	69
B292954		2.83	0.99	297	1	0.74	35	260	18	0.76	5	137	0.35	94	10	72
B292955		2.66	0.80	234	1	0.76	30	290	8	0.39	5	117	0.27	72	<10	49
B292956		0.03	12.10	154	<1	0.01	1	570	<2	0.01	<5	110	0.01	2	<10	8
B292957		1.88	0.84	291	<1	0.23	25	220	10	0.31	<5	102	0.23	53	10	45
B292958		2.92	0.86	407	<1	0.10	34	280	124	0.56	10	112	0.29	88	20	340
B292959		2.84	0.94	895	2	0.10	25	250	325	0.83	21	121	0.24	69	10	1600
B292960		3.18	0.73	740	<1	0.11	25	220	147	1.12	9	138	0.24	61	20	494
B292961		3.09	0.60	288	<1	0.07	23	160	69	1.96	29	63	0.23	65	20	99
B292962		2.62	0.59	292	<1	0.06	20	150	150	1.80	43	55	0.21	54	20	49
B292963		1.19	0.41	436	<1	0.03	14	180	101	0.22	12	178	0.16	32	10	247

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052041

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292964		5.72	0.061	0.7	6.60	1690	610	2.3	<2	1.06	2.4	5	17	25	1.56	0.13
B292965		3.36	0.066	0.5	7.30	1235	460	2.0	<2	1.54	<0.5	5	17	17	1.44	0.09
B292966		2.86	0.358	3.1	4.02	>10000	310	1.0	<2	0.64	3.3	24	29	85	4.21	0.17
B292967		2.14	0.051	2.2	6.42	2280	610	1.7	<2	0.47	1.2	7	51	293	3.33	0.09
B292968		2.14	2.46	28.3	6.71	>10000	150	1.7	5	0.16	<0.5	57	54	4510	10.65	0.15
B292969		0.04	2.45													
B292970		0.10	4.53	8.4	7.60	23	490	0.9	<2	2.89	1.2	17	26	128	4.37	0.02
B292971		1.16	0.254	2.7	6.44	>10000	790	1.4	4	2.62	<0.5	10	52	421	4.31	0.04
B292972		3.52	0.092	<0.5	7.83	4800	830	2.3	<2	0.39	<0.5	10	65	84	3.71	0.03
B292973		0.46	1.055	3.5	3.90	>10000	260	0.9	37	0.68	<0.5	87	34	62	12.10	0.03
B292974		2.70	0.067	<0.5	7.55	4140	700	2.2	<2	0.64	1.5	10	64	63	4.05	0.05
B292975		5.94	0.008	<0.5	8.36	178	800	2.3	<2	0.37	<0.5	14	73	27	4.29	0.02
B292976		1.80	<0.005	<0.5	0.15	6	20	<0.5	<2	19.00	<0.5	<1	3	2	0.14	<0.01
B292977		6.86	0.014	<0.5	9.24	148	860	2.8	<2	0.45	<0.5	13	82	28	4.19	0.03
B292978		6.20	0.009	<0.5	8.78	124	780	2.6	<2	0.48	<0.5	17	80	41	4.03	0.02
B292979		5.76	<0.005	<0.5	6.91	57	630	1.8	<2	0.71	<0.5	11	56	28	2.89	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 11-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052041

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292964		2.88	0.57	709	1	0.04	13	370	215	0.33	14	148	0.14	22	10	395
B292965		3.26	0.66	740	<1	0.03	11	370	51	0.24	14	112	0.14	23	10	43
B292966		1.73	0.36	831	<1	0.02	20	200	355	2.72	90	69	0.14	30	10	518
B292967		2.61	0.56	465	1	0.07	23	260	118	1.24	23	56	0.20	50	20	230
B292968		3.15	0.63	167	1	0.10	43	310	24	6.65	109	36	0.17	63	30	63
B292969																
B292970		2.31	1.40	973	12	1.84	14	920	20	0.70	5	415	0.38	150	<10	96
B292971		2.26	0.81	336	<1	0.34	21	280	22	1.68	30	132	0.15	40	20	32
B292972		2.93	0.76	298	<1	0.09	33	360	25	0.66	20	61	0.29	66	20	57
B292973		1.85	0.70	550	<1	0.03	34	100	647	6.01	308	46	0.10	32	20	49
B292974		3.33	0.99	527	<1	0.09	31	330	48	0.61	30	59	0.25	65	10	284
B292975		3.29	0.96	443	<1	0.27	43	360	8	0.14	16	98	0.37	77	20	75
B292976		0.04	11.40	149	<1	0.01	2	480	2	0.01	5	104	0.01	3	<10	12
B292977		4.47	0.97	404	1	0.79	42	430	18	0.32	7	134	0.41	89	30	82
B292978		3.60	1.03	360	<1	1.01	42	420	8	0.27	<5	148	0.39	81	10	70
B292979		2.61	0.84	340	<1	0.58	28	290	10	0.21	9	99	0.29	58	10	48

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-JUL-2005
Account: STRGOL

CERTIFICATE VA05052040

Project: Dublin Gulch-1735

P.O. No.:

This report is for 67 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 29-JUN-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052040

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B292980		4.70	0.006	<0.5	8.19	244	860	2.4	<2	0.29	<0.5	20	78	38	2.96	0.03
B292981		2.28	0.019	<0.5	8.59	266	1100	2.7	<2	0.18	<0.5	8	70	124	2.60	0.02
B292982		2.08	0.011	0.9	9.21	335	1090	2.9	<2	0.18	<0.5	5	94	79	2.88	0.02
B292983		1.42	0.017	<0.5	5.69	806	480	1.8	<2	0.17	<0.5	6	29	31	1.64	0.02
B292984		1.80	0.015	<0.5	3.59	435	360	1.1	<2	0.07	<0.5	2	88	19	1.25	0.01
B292985		2.12	0.051	<0.5	10.45	1740	1320	3.4	<2	0.22	<0.5	17	74	112	2.83	0.01
B292986		1.90	0.041	<0.5	8.39	837	1330	3.2	<2	0.92	<0.5	18	85	24	2.52	0.01
B292987		3.66	0.023	<0.5	8.30	497	930	3.3	<2	0.40	<0.5	13	53	37	2.85	0.01
B292988		3.26	0.011	<0.5	6.47	313	1000	2.1	<2	0.78	<0.5	4	48	6	0.99	0.02
B292989		0.04	0.011													
B292990		0.10	0.098	<0.5	6.78	110	560	2.5	<2	0.51	<0.5	59	1120	375	8.40	0.05
B292991		0.88	0.006	<0.5	7.94	539	1650	2.7	<2	0.71	<0.5	12	31	18	1.56	0.02
B292992		3.74	0.010	<0.5	8.83	331	990	3.0	<2	0.42	<0.5	14	83	50	3.31	0.01
B292993		1.96	0.006	<0.5	7.32	224	1410	2.6	<2	3.24	<0.5	20	131	18	3.43	0.01
B292994		3.20	0.008	<0.5	4.03	711	310	1.2	<2	0.27	<0.5	16	66	31	1.47	0.01
B292995		3.50	0.007	<0.5	4.11	259	250	0.9	<2	0.35	<0.5	7	24	25	1.79	0.01
B292996		1.68	<0.005	<0.5	0.11	<5	10	<0.5	<2	19.10	<0.5	<1	5	4	0.10	<0.01
B292997		3.90	<0.005	<0.5	7.63	114	730	2.2	<2	0.25	<0.5	18	55	49	3.54	0.03
B292998		5.50	<0.005	<0.5	8.67	183	940	2.4	<2	0.26	<0.5	15	86	45	3.49	0.03
B292999		4.46	<0.005	<0.5	7.63	187	800	2.0	<2	0.44	<0.5	12	51	40	2.88	0.01
B293000		2.70	0.008	<0.5	6.78	195	610	1.7	<2	0.31	<0.5	10	81	35	2.85	0.01
B380201		1.52	0.006	<0.5	9.82	262	1120	3.3	<2	0.28	<0.5	13	72	47	3.32	0.01
B380202		1.14	0.006	<0.5	9.30	187	1040	3.0	<2	0.31	<0.5	16	99	43	3.41	0.01
B380203		2.80	0.013	<0.5	7.61	243	870	2.4	<2	0.31	<0.5	12	58	39	2.49	0.01
B380204		3.60	0.007	<0.5	9.37	345	870	2.6	<2	0.28	<0.5	20	105	51	3.68	0.01
B380205		5.54	0.018	<0.5	5.26	312	430	1.1	<2	0.51	<0.5	8	38	23	2.09	0.01
B380206		5.52	0.010	<0.5	7.96	310	810	2.1	<2	0.36	<0.5	11	95	27	2.86	0.01
B380207		2.84	0.011	<0.5	5.57	218	510	1.5	<2	0.46	<0.5	8	42	30	2.41	0.01
B380208		3.08	0.007	<0.5	8.54	161	880	2.2	<2	0.27	<0.5	14	104	33	3.33	0.01
B380209		0.04	0.007													
B380210		0.10	0.469	2.1	8.67	7	1040	1.1	<2	1.42	<0.5	8	12	7120	3.26	0.04
B380211		1.52	0.038	<0.5	8.52	980	1010	2.4	<2	0.44	2.5	13	63	83	2.99	0.06
B380212		2.74	0.196	<0.5	4.21	2590	360	1.2	7	1.82	<0.5	6	96	102	2.03	0.02
B380213		2.92	0.017	<0.5	5.63	347	530	1.2	2	0.22	<0.5	6	40	22	2.03	0.01
B380214		2.78	0.009	<0.5	4.89	136	360	1.2	<2	0.34	<0.5	5	96	18	1.96	0.06
B380215		6.04	0.010	<0.5	6.86	124	730	1.9	<2	0.32	<0.5	7	52	34	2.62	0.04
B380216		1.84	<0.005	<0.5	0.12	<5	10	<0.5	<2	18.80	<0.5	<1	6	2	0.11	<0.01
B380217		4.80	0.006	<0.5	7.13	133	750	2.0	<2	0.41	<0.5	9	52	26	2.44	0.02
B380218		3.04	0.013	<0.5	4.14	184	290	1.1	<2	0.51	<0.5	3	97	16	1.70	0.02
B380219		2.98	0.021	<0.5	7.80	361	870	2.9	<2	0.50	<0.5	7	45	39	1.95	0.02

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052040

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B292980		3.96	0.97	158	<1	1.04	37	330	16	0.16	<5	144	0.33	94	<10	46
B292981		4.68	1.00	88	<1	1.11	8	350	15	0.12	<5	162	0.28	112	<10	48
B292982		5.01	1.03	94	<1	1.13	6	340	15	0.12	<5	157	0.30	112	<10	49
B292983		3.43	0.24	61	1	0.89	15	170	34	0.01	6	111	0.15	37	<10	49
B292984		1.57	0.28	60	1	0.31	6	130	9	0.01	<5	49	0.14	33	<10	20
B292985		5.70	0.79	98	1	0.87	25	310	21	0.10	8	162	0.39	114	10	30
B292986		4.08	0.96	170	2	1.37	60	530	28	0.09	6	279	0.34	66	10	48
B292987		4.67	0.93	168	1	1.12	33	260	29	0.10	<5	179	0.28	75	10	51
B292988		3.89	0.35	83	1	1.29	11	190	29	0.02	<5	232	0.12	20	<10	11
B292989																
B292990		2.18	0.58	371	8	0.12	479	340	152	0.02	13	51	0.22	89	30	603
B292991		4.49	0.51	152	2	1.29	43	320	26	0.06	<5	265	0.18	39	<10	25
B292992		4.90	1.12	182	1	1.20	34	320	23	0.18	<5	185	0.37	93	10	49
B292993		2.95	2.12	533	<1	1.36	66	770	26	0.05	<5	579	0.35	80	<10	71
B292994		1.90	0.35	167	1	0.61	38	200	12	0.04	<5	86	0.14	23	10	36
B292995		1.66	0.44	220	1	0.84	24	190	10	0.16	<5	95	0.13	24	<10	34
B292996		0.03	11.35	156	<1	0.01	1	520	2	0.01	<5	113	<0.01	2	<10	11
B292997		3.81	1.10	172	1	1.18	44	350	12	0.42	5	126	0.30	77	<10	50
B292998		4.52	1.09	163	1	1.20	35	380	18	0.51	5	142	0.29	87	<10	53
B292999		3.86	0.90	206	1	1.26	28	390	23	0.31	<5	149	0.26	75	10	46
B293000		3.53	0.77	231	3	1.07	25	260	19	0.17	<5	129	0.22	60	10	51
B380201		5.73	1.04	134	1	1.20	28	320	26	0.11	6	183	0.34	109	<10	44
B380202		5.71	1.08	161	1	1.14	38	300	23	0.10	6	178	0.31	99	10	48
B380203		4.60	0.74	146	<1	0.80	30	280	14	0.15	<5	134	0.25	79	30	30
B380204		4.61	1.04	200	1	1.07	53	460	17	0.32	<5	141	0.34	95	<10	62
B380205		2.35	0.61	212	1	0.91	18	240	11	0.10	<5	119	0.19	43	30	32
B380206		4.21	0.90	157	1	0.98	29	310	16	0.16	5	136	0.28	77	10	39
B380207		2.28	0.71	179	<1	0.63	22	270	9	0.26	<5	102	0.21	53	10	38
B380208		4.28	1.01	167	1	1.06	35	360	14	0.23	<5	133	0.34	88	<10	63
B380209																
B380210		3.70	1.14	476	3	3.45	9	1920	10	0.23	<5	690	0.33	170	<10	57
B380211		4.63	0.93	194	<1	0.89	38	370	78	0.26	<5	152	0.27	86	10	346
B380212		1.68	0.91	359	1	0.34	15	190	224	0.32	19	176	0.15	34	10	81
B380213		2.86	0.56	142	<1	0.66	20	280	12	0.06	5	101	0.20	45	20	48
B380214		2.13	0.54	180	<1	0.75	17	250	12	0.12	<5	92	0.18	36	10	43
B380215		3.75	0.83	160	<1	0.77	26	360	18	0.29	<5	102	0.24	65	<10	52
B380216		0.03	10.65	150	<1	0.01	3	510	3	0.01	<5	112	<0.01	1	<10	5
B380217		3.81	0.82	156	<1	0.94	25	340	19	0.20	<5	116	0.24	64	<10	45
B380218		1.98	0.46	190	<1	0.74	11	210	17	0.15	<5	101	0.14	25	10	31
B380219		5.03	0.75	125	1	1.10	22	300	35	0.31	<5	143	0.17	61	<10	20

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052040

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380220		4.42	0.014	<0.5	5.95	180	570	1.4	<2	0.36	<0.5	5	93	27	1.53	0.01
B380221		1.02	0.021	<0.5	6.15	83	590	1.5	<2	0.86	<0.5	7	46	27	2.48	0.02
B380222		1.26	0.008	<0.5	6.10	31	600	1.5	<2	0.79	<0.5	7	102	25	2.53	0.02
B380223		3.54	0.008	<0.5	5.32	154	470	1.3	<2	0.85	<0.5	5	34	15	1.80	0.01
B380224		5.36	0.037	<0.5	4.65	383	350	1.2	<2	0.88	<0.5	11	108	29	2.58	0.02
B380225		2.00	0.158	0.5	5.97	808	400	2.9	4	3.75	<0.5	15	37	148	6.48	0.30
B380226		4.84	0.006	<0.5	2.09	152	120	0.6	<2	0.86	<0.5	4	104	28	1.41	0.03
B380227		4.26	0.006	<0.5	1.60	209	60	<0.5	<2	0.60	<0.5	4	37	15	1.10	0.02
B380228		5.48	0.033	<0.5	1.56	212	50	<0.5	<2	0.51	<0.5	4	96	16	1.04	0.02
B380229		0.04	0.038													
B380230		0.12	0.870	2.3	7.43	24	430	0.7	<2	1.88	0.5	20	104	2040	4.99	0.05
B380231		5.78	0.017	<0.5	1.41	419	190	<0.5	<2	0.38	<0.5	2	32	15	1.01	0.01
B380232		4.28	0.024	<0.5	2.95	403	250	0.7	2	0.55	<0.5	5	108	42	1.13	0.01
B380233		5.76	0.062	<0.5	1.88	1080	270	0.5	3	1.13	<0.5	4	29	30	1.32	0.01
B380234		1.82	0.012	<0.5	1.76	165	100	<0.5	<2	1.30	<0.5	3	110	57	0.99	0.01
B380235		3.96	0.022	<0.5	7.67	490	820	2.0	3	1.10	<0.5	17	61	91	4.39	0.01
B380236		2.18	<0.005	<0.5	0.10	<5	10	<0.5	<2	18.85	<0.5	<1	7	2	0.10	<0.01
B380237		6.34	0.014	<0.5	7.57	267	910	2.6	<2	1.08	<0.5	14	64	83	3.63	0.01
B380238		4.54	0.060	<0.5	7.57	261	780	2.4	3	1.99	<0.5	13	87	72	3.85	0.02
B380239		2.78	0.044	<0.5	2.32	167	230	0.7	<2	1.53	<0.5	3	23	17	1.35	0.01
B380240		2.44	<0.005	<0.5	1.61	47	180	<0.5	<2	0.20	<0.5	2	98	9	0.82	0.01
B380241		0.96	0.007	<0.5	1.29	219	140	<0.5	<2	0.07	<0.5	2	23	13	0.84	0.01
B380242		1.12	0.008	<0.5	1.28	336	140	<0.5	<2	0.06	<0.5	2	110	14	0.87	0.02
B380243		5.72	<0.005	<0.5	1.36	37	80	<0.5	<2	0.04	<0.5	1	16	10	0.69	0.02
B380244		2.58	0.008	<0.5	1.60	200	20	<0.5	<2	0.04	<0.5	2	87	17	0.60	0.02
B380245		1.54	<0.005	<0.5	1.50	175	30	<0.5	<2	0.04	<0.5	2	27	13	1.32	0.06
B380246		4.12	0.074	<0.5	4.09	1125	340	1.0	4	0.13	<0.5	10	107	37	1.97	0.04

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05052040

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380220		3.34	0.48	120	1	0.72	17	220	19	0.20	<5	119	0.14	37	10	19
B380221		3.05	0.88	199	<1	0.71	23	310	12	0.23	<5	120	0.24	54	20	42
B380222		3.01	0.85	206	<1	0.74	23	290	16	0.26	5	112	0.22	51	30	42
B380223		2.94	0.66	181	<1	0.41	14	210	22	0.13	8	110	0.17	37	10	30
B380224		1.67	0.97	545	<1	0.44	25	300	16	0.17	<5	84	0.20	47	<10	53
B380225		1.88	2.78	1695	<1	0.12	47	580	7	1.15	10	233	0.30	71	80	83
B380226		0.56	0.41	303	<1	0.02	15	240	4	0.20	5	101	0.13	27	10	30
B380227		0.33	0.25	215	<1	0.01	14	250	6	0.08	<5	87	0.16	27	10	28
B380228		0.30	0.24	174	<1	0.01	12	180	5	0.10	<5	55	0.13	26	10	17
B380229																
B380230		1.72	1.29	425	2	3.13	49	660	20	0.60	<5	206	0.28	89	10	200
B380231		0.38	0.19	132	<1	0.02	6	130	3	0.11	<5	43	0.09	21	<10	12
B380232		1.04	0.26	160	1	0.04	18	160	8	0.29	<5	38	0.15	36	20	32
B380233		0.76	0.48	232	<1	0.04	9	170	6	0.30	<5	66	0.09	17	10	23
B380234		0.56	0.48	192	<1	0.37	12	140	5	0.34	<5	100	0.04	12	<10	8
B380235		3.60	1.66	761	3	0.72	47	550	12	0.82	<5	115	0.29	118	10	56
B380236		0.03	10.70	142	<1	0.01	6	470	4	0.01	<5	111	<0.01	1	10	5
B380237		4.82	1.35	519	2	0.67	38	500	9	0.76	<5	118	0.32	112	<10	51
B380238		3.66	1.92	697	<1	0.67	42	520	8	0.63	<5	155	0.33	96	10	54
B380239		0.99	0.51	363	<1	0.11	9	170	5	0.12	<5	57	0.11	26	20	21
B380240		0.76	0.18	158	<1	0.04	7	110	4	0.07	<5	18	0.07	19	10	13
B380241		0.62	0.10	140	<1	0.02	5	90	3	0.09	<5	11	0.06	16	10	10
B380242		0.62	0.10	155	<1	0.02	6	120	5	0.11	<5	10	0.06	16	10	11
B380243		0.42	0.07	130	<1	0.01	3	120	7	0.09	<5	8	0.06	17	10	20
B380244		0.19	0.06	127	<1	<0.01	5	120	6	0.05	<5	13	0.08	19	20	23
B380245		0.45	0.11	176	<1	<0.01	8	110	7	0.67	6	8	0.07	20	10	15
B380246		1.24	0.18	440	<1	0.04	28	280	10	0.50	<5	34	0.22	60	40	42

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da .4-JUL-2005
Account: STRGOL

CERTIFICATE VA05053956

Project: Dublin Gulch-1735

P.O. No.:

This report is for 85 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 5-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

094876

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05054218

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380247		4.20	<0.005	<0.5	1.46	22	50	<0.5	<2	0.06	<0.5	3	25	13	0.68	0.01
B380248		3.96	0.008	<0.5	1.57	160	60	<0.5	<2	0.07	<0.5	3	20	16	0.98	0.02
B380249		0.04	0.013													
B380250		0.10	2.86	<0.5	7.73	2120	770	13.5	<2	0.01	<0.5	1	147	101	3.53	0.08
B380251		5.96	0.011	<0.5	3.32	80	290	1.1	<2	1.17	<0.5	9	30	47	1.92	0.01
B380252		5.40	0.016	<0.5	6.47	49	580	2.3	<2	3.05	<0.5	15	34	39	2.82	<0.01
B380253		6.64	0.027	<0.5	7.69	509	860	2.5	<2	1.89	<0.5	22	55	66	4.26	0.01
B380254		5.62	0.017	<0.5	5.67	453	550	1.6	<2	1.08	<0.5	7	37	19	2.18	<0.01
B380255		5.96	0.104	<0.5	3.19	1085	290	0.8	6	0.38	<0.5	8	31	66	1.77	0.04
B380256		1.36	<0.005	<0.5	0.11	<5	10	<0.5	<2	18.15	<0.5	<1	2	4	0.10	<0.01
B380257		5.20	0.014	<0.5	1.89	171	30	<0.5	<2	0.14	<0.5	3	25	16	1.20	0.03
B380258		6.16	0.052	<0.5	1.90	1495	20	<0.5	3	0.09	<0.5	4	30	18	1.25	0.08
B380259		6.02	0.007	<0.5	1.77	234	50	<0.5	<2	0.07	<0.5	3	22	11	0.87	0.01
B380260		5.30	<0.005	<0.5	6.06	<5	420	0.8	<2	2.43	<0.5	10	41	24	3.06	0.01
B380261		2.88	0.007	<0.5	2.12	58	40	<0.5	<2	0.12	<0.5	6	29	20	1.06	0.02
B380262		2.74	0.018	<0.5	2.40	172	50	0.5	<2	0.10	<0.5	6	29	20	1.16	0.02
B380263		5.80	0.071	<0.5	1.76	147	60	<0.5	4	0.30	<0.5	3	24	22	0.92	0.03
B380264		5.14	0.153	<0.5	3.62	588	280	0.7	5	0.37	<0.5	9	35	69	2.13	0.03
B380265		5.20	0.153	<0.5	3.44	871	440	0.8	6	0.69	<0.5	8	33	57	1.76	<0.01
B380266		6.06	0.106	<0.5	3.70	1130	470	0.9	<2	0.71	<0.5	6	34	39	1.52	<0.01
B380267		5.60	0.058	<0.5	4.73	878	590	1.5	<2	0.89	<0.5	10	40	56	1.95	0.01
B380268		5.38	0.025	<0.5	5.06	825	620	1.7	<2	0.69	<0.5	9	40	200	2.50	0.01
B380269		0.04	0.028													
B380270		0.10	2.85	<0.5	7.68	2020	750	13.0	<2	0.01	<0.5	2	144	99	3.43	0.07
B380271		5.76	0.037	<0.5	1.94	343	140	0.7	<2	0.83	<0.5	4	26	26	0.89	0.01
B380272		5.64	<0.005	<0.5	6.72	7	500	0.8	<2	2.73	<0.5	12	48	30	3.43	0.01
B380273		3.84	0.062	<0.5	2.45	355	340	0.8	<2	0.91	<0.5	5	25	25	1.43	0.01
B380274		2.28	0.517	<0.5	6.00	3700	890	1.8	<2	2.17	<0.5	9	21	7	1.72	0.01
B380275		1.58	0.714	<0.5	6.63	>10000	1080	2.0	<2	1.08	<0.5	16	17	3	1.92	0.01
B380276		1.94	0.005	<0.5	0.13	7	30	<0.5	<2	19.40	<0.5	1	3	2	0.14	<0.01
B380277		4.26	0.250	<0.5	6.92	2570	1230	2.7	<2	1.45	<0.5	9	17	18	1.72	0.01
B380278		3.10	0.573	<0.5	7.32	6220	1470	1.9	3	0.85	<0.5	10	15	2	1.38	0.01
B380279		4.60	0.085	<0.5	2.68	1380	320	0.8	<2	0.54	<0.5	6	26	26	1.15	0.02
B380280		5.06	0.056	<0.5	2.72	985	160	0.6	2	0.53	<0.5	5	24	14	0.88	0.02
B380281		1.26	0.053	<0.5	3.26	1775	100	0.7	3	0.70	<0.5	6	27	21	1.18	0.02
B380282		1.46	0.090	<0.5	2.62	3560	110	0.6	4	0.95	<0.5	5	25	19	1.49	0.03
B380283		2.12	0.005	<0.5	1.68	47	80	<0.5	<2	0.53	2.2	3	15	13	0.85	0.01
B380284		2.90	0.050	<0.5	7.10	496	930	2.3	<2	0.77	<0.5	17	59	83	3.81	0.02
B380285		4.00	0.005	<0.5	7.35	48	770	2.4	<2	0.58	<0.5	11	51	30	3.22	0.01
B380286		4.36	0.150	<0.5	5.47	3830	560	1.3	<2	0.85	<0.5	14	34	41	2.18	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380301		2.52	0.006	<0.5	7.10	176	620	1.9	<2	0.72	<0.5	14	51	33	2.84	0.04
B380302		3.36	0.011	<0.5	7.21	172	570	1.9	<2	1.08	<0.5	13	81	36	2.98	0.03
B380303		2.34	0.032	<0.5	5.15	1660	370	1.4	<2	0.76	<0.5	12	35	23	1.96	0.08
B380304		3.46	0.113	<0.5	6.06	3720	740	1.0	2	0.76	<0.5	16	52	5	1.34	0.02
B380305		5.72	0.010	<0.5	6.87	539	560	1.8	<2	0.37	<0.5	13	54	31	2.80	0.02
B380306		5.44	0.009	<0.5	5.06	383	380	1.3	<2	0.82	<0.5	9	68	15	2.10	0.01
B380307		4.00	0.087	0.5	6.97	1220	1210	2.5	5	1.79	<0.5	10	33	45	2.48	0.01
B380308		2.82	0.192	<0.5	7.26	3370	1290	2.8	7	2.15	<0.5	9	54	27	2.21	0.01
B380309		0.04	0.201													
B380310		0.10	4.42	9.3	7.81	13	470	0.9	<2	2.75	1.1	19	22	118	4.01	0.01
B380311		3.04	0.240	3.0	7.33	2990	600	2.7	7	2.64	1.9	8	21	42	2.86	0.02
B380312		3.32	0.187	3.9	7.52	4020	720	2.9	9	2.19	2.3	8	58	55	2.52	0.03
B380313		4.24	0.138	<0.5	7.56	2030	1490	2.8	4	2.11	<0.5	9	26	37	2.48	0.01
B380314		4.10	0.247	1.1	7.08	5100	1280	2.7	14	1.91	1.0	10	57	39	2.55	0.02
B380315		1.80	0.179	1.0	6.80	3950	940	2.7	7	2.46	0.5	9	23	30	2.05	0.02
B380316		1.44	<0.005	<0.5	0.11	15	20	<0.5	<2	20.2	<0.5	2	5	2	0.11	<0.01
B380317		2.18	0.276	1.0	7.30	6960	1280	2.5	8	2.52	0.6	9	23	40	2.50	0.01
B380318		4.72	0.145	<0.5	7.17	2160	1590	2.7	7	2.80	<0.5	9	55	40	2.25	0.01
B380319		6.64	0.291	0.5	7.78	3720	1640	2.7	11	2.43	<0.5	12	26	33	2.32	<0.01
B380320		3.80	0.177	1.9	6.57	4040	1180	2.5	9	2.33	6.7	8	55	61	2.74	0.11
B380321		0.44	1.080	4.2	0.74	6930	40	0.5	34	2.49	0.5	13	9	10	6.84	0.03
B380322		0.50	0.359	1.8	0.84	4280	40	0.6	8	2.18	0.6	7	61	8	3.57	0.02
B380323		5.98	0.182	<0.5	7.71	3000	1780	2.8	8	2.05	<0.5	10	29	29	2.41	0.01
B380324		5.86	0.354	0.6	7.47	5710	1620	2.8	12	2.42	<0.5	10	56	24	2.34	<0.01
B380325		4.26	0.181	0.5	7.38	3070	1730	3.1	9	2.29	<0.5	10	30	34	2.53	<0.01
B380326		6.10	0.132	0.8	7.86	2800	1450	3.0	10	2.38	<0.5	10	49	31	2.29	0.01
B380327		5.42	0.180	<0.5	7.51	3260	1370	2.9	5	2.23	<0.5	11	27	34	2.31	0.01
B380328		5.34	0.165	<0.5	7.76	2590	1450	2.9	8	2.14	<0.5	10	50	30	2.05	<0.01
B380329		0.04	0.179													
B380330		0.10	0.425	3.5	8.79	6	1100	1.2	<2	1.50	<0.5	10	9	7460	5.21	0.02
B380331		1.40	0.213	<0.5	7.13	3100	1340	2.9	6	2.46	<0.5	10	27	27	2.06	0.01
B380332		4.36	0.076	<0.5	7.51	1530	1490	2.9	2	2.24	<0.5	9	51	22	2.25	<0.01
B380333		2.92	0.089	0.5	7.38	2010	1530	3.0	6	2.14	<0.5	10	28	28	2.44	<0.01
B380334		6.62	0.142	0.5	7.91	1585	1650	3.1	6	2.21	<0.5	10	58	31	2.36	0.01
B380335		5.96	0.144	<0.5	7.00	1845	1240	2.4	8	2.06	<0.5	8	24	19	2.09	<0.01
B380336		1.34	<0.005	<0.5	0.11	5	20	<0.5	<2	20.3	<0.5	1	5	1	0.11	<0.01
B380337		10.54	0.048	<0.5	7.58	773	1600	2.9	4	2.45	<0.5	9	28	34	2.35	0.01
B380338		7.00	0.069	<0.5	7.47	841	1520	2.9	3	2.48	<0.5	10	48	31	2.18	0.01
B380339		6.20	0.325	<0.5	7.75	3050	1680	2.8	20	2.47	<0.5	9	34	36	2.38	<0.01
B380340		3.02	0.212	<0.5	7.59	2260	1480	3.0	6	2.31	<0.5	12	59	33	2.39	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380301		3.08	0.89	252	<1	0.55	33	270	16	0.32	7	128	0.26	67	<10	55
B380302		2.84	0.98	270	<1	0.61	26	260	20	0.35	<5	134	0.26	64	10	47
B380303		2.26	0.61	158	<1	0.44	22	220	20	0.38	9	95	0.16	41	<10	49
B380304		4.15	0.45	116	<1	0.80	13	300	39	0.22	5	139	0.07	17	<10	15
B380305		2.67	0.78	264	<1	0.49	31	260	16	0.35	5	91	0.26	66	10	58
B380306		1.74	0.66	297	<1	0.22	15	210	20	0.23	8	113	0.19	40	<10	48
B380307		3.14	0.76	322	<1	1.01	19	540	35	0.25	9	252	0.29	49	10	44
B380308		3.83	0.66	427	1	0.76	20	570	39	0.32	22	255	0.26	33	40	49
B380309																
B380310		2.18	1.30	950	11	1.58	14	860	30	0.68	<5	405	0.36	145	<10	97
B380311		3.27	0.72	1235	<1	0.03	19	580	322	1.32	35	106	0.24	32	20	328
B380312		3.50	0.67	972	<1	0.04	23	610	374	1.16	52	105	0.25	37	30	375
B380313		3.93	0.74	378	<1	1.07	19	610	36	0.29	19	300	0.28	35	20	48
B380314		3.43	0.73	371	1	0.87	19	550	148	0.68	14	291	0.25	33	40	182
B380315		4.13	0.56	642	<1	0.20	16	610	60	0.29	16	181	0.27	34	50	134
B380316		0.03	11.50	156	<1	0.01	1	520	4	0.01	<5	113	<0.01	1	<10	8
B380317		4.04	0.76	621	<1	0.58	15	550	100	0.55	26	272	0.24	32	20	136
B380318		3.65	0.78	262	<1	1.28	18	610	26	0.33	10	425	0.29	39	30	34
B380319		3.96	0.72	315	<1	0.99	21	640	36	0.41	12	343	0.29	37	30	46
B380320		3.36	0.74	1155	1	0.44	20	590	336	0.98	83	220	0.25	33	20	1130
B380321		0.26	0.56	2530	<1	0.02	14	40	577	6.25	177	105	0.02	4	<10	104
B380322		0.32	0.49	1910	<1	0.01	9	60	114	2.81	41	102	0.02	4	10	120
B380323		3.82	0.75	281	<1	1.32	24	650	29	0.30	10	387	0.30	38	40	36
B380324		3.90	0.74	269	<1	1.19	20	610	39	0.42	9	380	0.28	36	50	43
B380325		3.61	0.84	259	<1	1.52	22	670	30	0.33	5	450	0.31	39	20	41
B380326		3.74	0.79	349	<1	1.15	20	630	38	0.33	<5	369	0.28	36	20	53
B380327		3.52	0.78	299	<1	1.25	18	590	36	0.35	<5	351	0.27	35	20	45
B380328		3.88	0.68	202	<1	1.28	22	590	29	0.27	<5	370	0.27	33	40	39
B380329																
B380330		3.68	1.14	491	1	3.42	12	1940	21	0.25	<5	691	0.34	176	<10	62
B380331		3.48	0.75	186	<1	1.35	21	610	25	0.25	<5	352	0.27	34	20	31
B380332		3.34	0.78	243	<1	1.56	22	620	29	0.17	<5	431	0.29	36	20	50
B380333		3.70	0.77	313	1	1.33	22	650	33	0.22	11	398	0.31	39	20	59
B380334		3.53	0.82	259	1	1.49	22	620	30	0.20	<5	411	0.30	38	20	50
B380335		3.63	0.71	210	<1	1.39	16	540	30	0.16	<5	320	0.24	30	20	33
B380336		0.03	11.60	151	<1	0.01	<1	560	2	0.02	<5	113	<0.01	1	<10	7
B380337		3.43	0.77	219	<1	1.31	20	630	24	0.19	<5	370	0.29	36	30	38
B380338		3.48	0.73	247	<1	1.37	22	620	23	0.17	<5	374	0.29	36	20	40
B380339		3.58	0.74	192	<1	1.37	20	650	22	0.27	6	401	0.31	42	50	27
B380340		3.42	0.76	218	<1	1.32	24	710	20	0.26	5	386	0.34	46	40	41

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

094870

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380341		1.66	0.089	<0.5	7.85	410	1660	2.8	2	2.23	<0.5	8	34	19	2.36	0.01
B380342		1.64	0.109	<0.5	7.76	741	1660	2.8	3	2.39	<0.5	7	51	19	2.33	0.01
B380343		4.78	0.210	<0.5	7.71	3480	1620	2.9	4	2.65	<0.5	8	35	22	2.87	0.02
B380344		3.26	0.115	<0.5	7.41	1625	1390	2.5	<2	1.72	<0.5	9	53	30	2.86	0.05
B380345		4.42	0.028	<0.5	4.01	490	410	1.1	<2	0.87	<0.5	6	33	41	1.61	0.03
B380346		5.30	0.104	0.7	4.73	2360	620	1.2	2	0.43	0.6	7	71	42	1.53	0.08
B380347		5.14	0.068	<0.5	3.32	957	470	0.9	<2	0.72	<0.5	7	34	55	1.70	0.07
B380348		1.22	0.082	<0.5	1.88	1020	150	0.5	3	1.10	<0.5	4	60	26	1.14	0.01
B380349		0.04	0.078													
B380350		0.10	0.089	0.5	6.69	110	590	2.5	<2	0.51	<0.5	55	1165	386	8.40	0.03
B380351		2.00	0.014	0.5	1.49	639	100	<0.5	<2	0.64	0.6	2	50	13	0.72	0.02
B380352		2.24	0.015	<0.5	1.59	696	90	<0.5	2	0.45	<0.5	2	23	13	0.95	0.01
B380353		0.92	0.074	<0.5	2.49	1050	300	0.8	3	2.06	<0.5	5	61	27	1.77	0.01
B380354		3.22	0.070	<0.5	7.76	2410	1390	2.6	<2	2.62	<0.5	13	31	19	2.38	0.01
B380355		3.06	0.046	<0.5	7.63	1240	1430	2.9	<2	2.00	<0.5	9	54	26	2.45	0.01
B380356		2.34	<0.005	<0.5	0.13	10	30	<0.5	<2	19.95	<0.5	<1	2	1	0.13	<0.01
B380357		2.18	0.016	<0.5	3.07	228	310	1.1	<2	1.71	<0.5	3	55	14	1.44	0.01
B380358		4.02	0.037	<0.5	7.10	1450	1500	2.1	<2	1.79	<0.5	9	24	11	2.03	0.02
B380359		2.84	0.049	<0.5	7.75	1290	1670	2.8	<2	1.34	<0.5	10	53	14	2.58	0.02
B380360		4.48	0.028	<0.5	7.44	768	1240	1.7	<2	0.70	<0.5	9	57	10	1.65	0.02
B380361		0.74	0.006	<0.5	5.17	180	760	1.4	<2	1.12	<0.5	4	22	12	1.93	0.01
B380362		0.60	0.012	<0.5	5.49	145	750	1.6	<2	1.61	2.0	5	51	25	2.28	0.05
B380363		2.44	0.012	<0.5	5.51	155	600	1.6	<2	1.01	<0.5	7	33	21	2.64	0.01
B380364		6.36	0.046	0.8	5.21	1450	370	1.6	<2	0.27	<0.5	8	32	95	4.41	0.01
B380365		3.58	0.049	<0.5	3.93	798	370	1.1	<2	0.81	<0.5	5	59	33	2.04	0.01
B380366		1.46	0.038	<0.5	7.90	568	1220	2.1	<2	1.97	<0.5	10	26	24	2.59	0.03
B380367		1.78	0.047	<0.5	7.59	780	1500	2.3	<2	1.77	<0.5	11	52	26	2.43	0.05
B380368		4.88	0.054	<0.5	6.81	1200	1440	2.5	<2	1.71	<0.5	9	29	29	2.48	0.03
B380369		0.04	0.054													
B380370		0.10	0.880	2.2	7.82	12	480	0.7	<2	1.99	1.0	23	99	2100	5.34	<0.01
B380371		2.84	0.021	<0.5	7.20	922	1390	2.7	<2	2.05	<0.5	9	53	23	2.26	0.03
B380372		3.58	0.030	<0.5	7.62	898	1750	2.1	<2	1.52	<0.5	8	20	10	1.90	0.05
B380373		1.78	0.288	7.4	6.28	3330	170	2.0	11	0.82	<0.5	13	55	110	8.35	0.08
B380374		2.54	0.026	<0.5	6.84	765	840	2.0	<2	1.26	<0.5	7	42	42	3.03	0.03
B380375		3.16	0.151	<0.5	7.78	2690	1960	2.8	<2	2.06	<0.5	14	51	17	2.15	0.02
B380376		2.10	<0.005	<0.5	0.13	10	20	<0.5	<2	20.2	<0.5	<1	4	1	0.13	<0.01
B380377		5.10	0.034	<0.5	6.09	900	1310	1.7	<2	1.17	<0.5	5	25	6	1.31	0.01
B380378		2.36	0.037	<0.5	8.22	736	1350	2.8	<2	1.03	<0.5	11	62	55	2.46	0.03
B380379		3.02	0.010	<0.5	7.36	158	580	2.0	7	0.73	<0.5	11	61	31	2.67	0.01
B380380		5.58	0.007	<0.5	8.13	134	740	2.7	4	0.77	<0.5	11	87	42	3.05	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380341		3.27	0.80	237	<1	1.66	13	640	15	0.10	<5	384	0.28	47	20	39
B380342		3.18	0.78	248	<1	1.62	14	640	18	0.11	<5	395	0.27	46	30	36
B380343		3.49	0.83	345	<1	1.48	13	660	18	0.26	<5	458	0.29	50	40	44
B380344		3.38	0.92	386	<1	0.46	16	720	41	0.30	13	237	0.30	52	30	74
B380345		1.99	0.42	220	1	0.06	14	220	21	0.23	9	126	0.16	39	20	38
B380346		2.77	0.25	233	2	0.10	19	230	50	0.18	18	130	0.17	52	20	126
B380347		1.71	0.32	283	1	0.07	22	220	14	0.20	8	80	0.16	40	40	51
B380348		0.76	0.44	275	1	0.02	11	150	8	0.21	8	74	0.10	16	30	30
B380349																
B380350		2.16	0.58	382	9	0.11	484	340	144	0.02	15	48	0.23	89	30	602
B380351		0.68	0.24	358	<1	0.01	7	150	60	0.10	9	34	0.09	18	10	101
B380352		0.32	0.24	195	<1	0.01	9	180	45	0.08	13	166	0.11	22	10	33
B380353		1.35	1.12	350	1	0.09	20	240	3	0.18	7	211	0.11	28	80	39
B380354		3.96	1.15	385	2	0.90	33	770	29	0.21	8	246	0.29	48	20	197
B380355		3.55	1.01	236	1	1.13	27	780	16	0.30	9	338	0.32	49	10	114
B380356		0.04	11.65	165	<1	0.01	5	610	2	0.01	<5	109	0.01	3	<10	8
B380357		1.70	0.70	199	<1	0.15	8	220	16	0.15	7	134	0.12	23	10	44
B380358		3.32	1.03	290	1	0.48	25	700	19	0.11	14	206	0.29	38	20	79
B380359		3.00	0.96	273	1	0.92	28	810	17	0.12	13	277	0.34	45	20	104
B380360		2.88	0.46	315	1	0.17	25	640	28	0.07	17	122	0.27	41	20	151
B380361		2.53	0.59	352	<1	0.07	14	310	25	0.09	9	87	0.18	28	10	90
B380362		2.76	0.78	477	1	0.08	15	300	97	0.34	11	99	0.18	28	10	402
B380363		2.24	0.68	462	1	0.09	21	250	22	0.11	19	94	0.21	44	10	95
B380364		2.44	0.63	400	1	0.04	17	240	23	2.10	11	29	0.18	43	20	52
B380365		1.88	0.48	202	1	0.11	12	220	27	0.74	5	73	0.14	23	10	36
B380366		4.51	0.90	316	1	0.10	28	710	29	0.25	10	164	0.30	40	<10	67
B380367		4.06	0.88	235	1	0.81	34	780	25	0.28	14	222	0.31	42	30	52
B380368		3.90	0.85	223	<1	0.77	28	780	17	0.41	21	216	0.33	43	20	34
B380369																
B380370		1.76	1.38	454	3	3.10	54	680	12	0.61	<5	207	0.31	93	<10	206
B380371		3.44	0.84	245	2	1.01	27	720	19	0.30	16	264	0.29	40	20	39
B380372		3.86	0.69	213	1	0.93	24	680	22	0.12	16	244	0.26	31	20	41
B380373		3.14	0.53	154	2	0.51	23	380	1695	7.97	336	116	0.18	33	20	58
B380374		3.49	0.98	320	1	0.23	29	330	40	0.17	24	126	0.28	58	20	74
B380375		3.67	0.86	132	1	1.43	35	780	24	0.23	10	363	0.27	40	20	19
B380376		0.04	11.80	174	<1	0.01	3	600	3	0.01	<5	107	0.01	3	<10	7
B380377		3.38	0.50	89	1	1.01	15	380	21	0.07	<5	220	0.15	22	40	11
B380378		4.97	0.73	162	1	1.10	29	300	40	0.51	5	201	0.26	66	10	30
B380379		3.09	0.78	266	<1	0.94	27	230	3	0.36	<5	129	0.28	70	10	54
B380380		3.31	0.93	281	1	1.44	33	240	16	0.33	<5	168	0.30	87	10	49

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380381		1.72	0.021	<0.5	7.31	321	690	2.1	6	0.84	<0.5	11	56	44	2.65	<0.01
B380382		1.20	0.013	<0.5	7.00	335	640	2.1	2	0.88	<0.5	10	80	45	2.56	<0.01
B380383		6.12	0.027	<0.5	7.51	761	1120	2.5	3	1.40	<0.5	7	29	11	1.39	0.01
B380384		2.60	0.024	<0.5	7.27	150	630	2.0	<2	0.64	<0.5	10	78	46	2.69	0.02
B380385		5.56	0.008	<0.5	8.35	235	830	2.1	<2	0.91	<0.5	13	63	38	3.29	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 14-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05053956

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380381		3.58	0.81	204	<1	1.12	32	220	9	0.42	<5	154	0.27	71	<10	35
B380382		3.21	0.78	201	<1	1.06	28	220	16	0.41	7	146	0.26	65	<10	34
B380383		4.09	0.62	106	<1	1.55	14	240	32	0.10	<5	261	0.16	32	<10	17
B380384		3.16	0.61	210	<1	1.14	25	180	13	0.67	6	143	0.27	62	<10	35
B380385		3.34	0.92	317	<1	1.37	31	830	12	0.41	<5	185	0.44	94	10	48

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 5-JUL-2005
Account: STRGOL

CERTIFICATE VA05055092

Project: Dublin Gulch-1735

P.O. No.:

This report is for 7 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 7-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 15-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055092

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B292494		4.94	0.042	<0.5	6.99	91	1550	2.9	<2	1.73	<0.5	9	28	26	2.32	0.03
B292495		6.94	1.875	<0.5	6.43	169	1470	2.8	37	2.19	<0.5	10	26	49	2.23	0.02
B292496		1.92	<0.005	<0.5	0.13	<5	20	<0.5	<2	17.90	<0.5	1	5	4	0.14	<0.01
B292497		4.94	0.328	<0.5	6.44	296	1260	3.0	14	1.63	<0.5	12	25	60	2.19	0.02
B292498		6.42	0.158	<0.5	6.83	405	1470	2.8	3	1.67	<0.5	10	51	49	2.27	0.02
B292499		4.78	1.380	<0.5	6.88	249	1420	2.8	35	1.74	<0.5	14	46	37	2.34	0.02
B292500		2.82	0.550	1.1	6.86	452	1070	2.7	17	2.34	6.2	12	51	105	2.25	0.15

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 15-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055092

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B292494		3.60	0.97	243	1	1.30	18	600	25	0.10	<5	461	0.30	35	20	53
B292495		3.60	0.95	236	4	1.11	16	570	23	0.17	5	404	0.29	35	30	45
B292496		0.03	11.05	144	<1	0.01	3	550	3	0.01	<5	105	0.01	3	<10	7
B292497		3.83	0.71	205	1	1.42	14	490	27	0.36	<5	368	0.25	30	30	43
B292498		3.82	0.86	239	1	1.33	17	560	28	0.27	8	430	0.27	34	30	53
B292499		3.40	0.71	254	1	1.35	17	580	49	0.19	15	382	0.28	35	10	66
B292500		3.75	0.38	489	5	0.63	19	560	338	0.73	169	192	0.25	32	50	1010

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 6-JUL-2005
Account: STRGOL

CERTIFICATE VA05055093

Project: Dublin Gulch-1735

P.O. No.:

This report is for 57 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 7-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055093

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380386		5.18	0.024	<0.5	7.50	278	720	1.8	<2	0.77	<0.5	11	152	50	2.79	0.02
B380387		3.26	0.007	<0.5	9.90	61	1000	2.8	<2	0.50	<0.5	16	80	42	4.11	0.01
B380388		2.32	0.007	<0.5	6.98	92	670	1.7	<2	1.12	<0.5	9	144	24	2.99	0.01
B380389		0.04	0.008													
B380390		0.10	0.418	2.4	9.32	7	1080	1.1	<2	1.53	<0.5	8	8	7220	3.30	0.03
B380391		5.18	0.041	<0.5	7.26	870	880	1.9	<2	0.84	<0.5	11	48	76	2.21	<0.01
B380392		4.26	0.038	<0.5	6.83	430	670	1.6	<2	1.10	<0.5	12	67	54	2.39	0.01
B380393		3.48	0.023	<0.5	7.49	481	1310	2.6	<2	3.22	<0.5	13	92	47	3.58	0.02
B380394		3.50	0.023	<0.5	7.12	548	1370	2.3	2	3.01	<0.5	14	78	22	3.61	0.04
B380395		5.32	0.008	<0.5	8.81	174	660	2.1	<2	2.38	<0.5	11	72	30	2.97	0.01
B380396		5.56	0.012	<0.5	8.55	215	780	2.1	<2	1.51	<0.5	12	138	65	3.07	0.01
B380397		1.70	0.014	<0.5	7.68	566	1350	2.4	3	3.10	<0.5	15	82	29	3.53	0.02
B380398		4.96	0.053	<0.5	7.94	977	1040	2.3	6	3.65	<0.5	14	95	38	3.78	0.01
B380399		2.24	0.075	<0.5	7.42	1880	710	1.9	<2	1.63	<0.5	16	120	82	2.78	0.01
B380400		3.50	0.029	<0.5	6.73	679	760	1.4	<2	1.38	<0.5	8	79	54	2.40	0.01
B380401		3.18	0.018	<0.5	6.78	482	820	1.9	<2	2.10	<0.5	12	78	38	3.10	0.01
B380402		3.16	0.011	<0.5	7.56	255	850	1.9	<2	2.05	<0.5	14	131	40	3.07	0.01
B380403		6.06	0.010	<0.5	7.80	491	760	1.9	<2	0.70	<0.5	13	101	36	3.07	0.01
B380404		5.62	0.019	<0.5	7.69	610	790	1.8	<2	0.56	<0.5	10	79	33	2.76	0.01
B380405		7.20	0.064	<0.5	8.60	1430	950	2.0	2	0.83	<0.5	18	63	65	3.34	0.01
B380406		4.94	<0.005	<0.5	8.02	36	780	1.9	<2	0.64	<0.5	13	135	31	3.44	0.01
B380407		4.74	<0.005	<0.5	7.92	100	740	1.8	<2	0.70	<0.5	14	95	32	3.08	0.01
B380408		5.56	0.007	<0.5	9.30	129	790	2.3	<2	0.56	<0.5	14	69	46	3.54	0.01
B380409		0.04	0.008													
B380410		0.10	0.089	<0.5	7.24	103	580	2.6	<2	0.52	<0.5	59	1170	398	8.43	0.03
B380411		6.28	<0.005	<0.5	7.89	180	640	1.9	<2	0.69	<0.5	13	90	31	3.41	<0.01
B380412		6.34	0.020	<0.5	6.07	569	750	1.4	2	0.95	<0.5	11	146	32	2.65	0.01
B380413		5.80	0.024	<0.5	7.23	1155	620	1.7	<2	0.58	<0.5	14	99	23	3.16	0.01
B380414		5.98	0.017	<0.5	8.30	576	810	1.9	2	0.52	<0.5	16	68	34	3.48	0.01
B380415		0.82	0.039	<0.5	8.39	1180	670	2.0	<2	0.57	<0.5	17	93	28	3.50	0.01
B380416		1.80	<0.005	<0.5	0.16	<5	20	<0.5	<2	20.6	<0.5	1	5	2	0.14	<0.01
B380417		5.14	0.005	<0.5	6.55	279	510	1.5	<2	0.55	<0.5	11	96	26	2.67	0.01
B380418		4.42	<0.005	<0.5	5.55	334	420	1.3	<2	0.57	<0.5	10	141	28	2.31	0.02
B380419		6.12	0.008	<0.5	7.90	267	730	1.8	<2	1.14	<0.5	24	171	34	4.05	0.02
B380420		5.42	0.010	<0.5	4.84	199	400	1.0	<2	0.62	<0.5	10	56	14	2.12	0.01
B380421		2.92	0.012	<0.5	7.40	213	680	1.6	<2	0.49	<0.5	12	86	34	2.80	0.03
B380422		2.46	0.020	<0.5	7.92	505	750	1.7	<2	0.52	0.5	13	94	37	2.88	0.03
B380423		3.14	<0.005	<0.5	8.86	49	740	2.1	<2	0.50	<0.5	14	129	48	3.46	0.04
B380424		2.80	<0.005	<0.5	3.03	59	260	0.6	<2	0.17	<0.5	5	30	5	1.52	0.02
B380425		3.64	<0.005	<0.5	3.95	175	300	0.8	<2	0.45	<0.5	7	91	9	1.64	0.02

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055093

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380386		3.01	0.77	261	4	1.41	30	320	19	0.40	<5	180	0.29	65	<10	47
B380387		3.98	0.97	411	1	1.08	39	300	10	0.46	<5	159	0.40	102	<10	62
B380388		2.72	0.93	423	1	0.79	26	380	11	0.32	<5	151	0.24	59	<10	37
B380389																
B380390		3.62	1.19	484	2	3.30	11	1930	11	0.24	<5	686	0.34	163	<10	57
B380391		4.10	0.75	157	<1	0.99	30	300	21	0.51	<5	141	0.14	59	<10	22
B380392		3.13	0.80	230	1	0.79	31	320	15	0.50	<5	127	0.18	50	<10	26
B380393		2.75	1.69	516	1	1.21	21	840	9	0.34	<5	439	0.40	81	20	62
B380394		2.48	1.62	568	1	0.96	21	850	7	0.34	<5	379	0.39	81	10	59
B380395		4.11	1.18	365	1	0.83	36	340	14	0.43	<5	164	0.34	71	10	54
B380396		3.66	0.98	303	<1	0.77	37	450	11	0.91	<5	138	0.29	67	<10	46
B380397		2.49	1.45	678	<1	0.91	20	870	8	0.79	<5	368	0.40	82	<10	57
B380398		2.36	1.72	719	2	0.88	22	860	6	0.79	<5	328	0.40	80	40	59
B380399		2.69	1.06	253	1	0.68	29	480	8	0.66	<5	147	0.23	58	<10	26
B380400		3.54	0.92	201	<1	0.76	27	280	12	0.39	5	152	0.15	44	<10	15
B380401		2.70	1.56	626	3	0.76	31	420	10	0.47	5	155	0.29	72	10	40
B380402		2.97	1.60	600	2	0.84	31	400	9	0.45	5	172	0.31	78	10	36
B380403		3.23	0.90	364	<1	0.96	33	310	10	0.42	<5	130	0.35	65	10	31
B380404		4.00	0.78	276	<1	0.99	29	330	21	0.33	<5	156	0.30	54	10	29
B380405		3.68	1.00	430	<1	0.78	40	550	10	0.66	<5	138	0.31	68	10	35
B380406		2.78	0.84	471	<1	0.94	29	250	16	0.48	<5	113	0.34	63	<10	47
B380407		3.29	0.88	427	<1	0.98	27	250	25	0.31	<5	139	0.34	58	10	47
B380408		3.93	1.02	388	<1	0.83	40	500	13	0.31	<5	135	0.35	73	<10	53
B380409																
B380410		2.20	0.59	390	7	0.12	485	360	151	0.03	13	51	0.25	95	30	618
B380411		2.75	0.90	432	<1	0.95	32	420	13	0.25	<5	123	0.34	67	<10	59
B380412		2.12	0.72	321	1	0.98	27	320	11	0.22	<5	131	0.25	45	10	40
B380413		2.58	0.82	310	<1	0.92	30	300	11	0.21	<5	117	0.29	60	10	49
B380414		3.27	0.94	344	<1	0.95	37	320	11	0.29	<5	126	0.34	70	<10	60
B380415		3.61	0.96	309	1	0.97	37	370	8	0.27	<5	161	0.34	69	10	59
B380416		0.05	12.10	193	<1	0.01	3	550	3	0.01	<5	125	<0.01	2	<10	6
B380417		2.21	0.71	284	<1	0.70	28	270	10	0.20	<5	111	0.27	51	10	44
B380418		1.88	0.68	272	<1	0.77	23	200	24	0.18	<5	97	0.23	44	10	36
B380419		3.32	1.80	455	<1	0.75	140	310	14	0.39	<5	125	0.32	76	10	69
B380420		1.58	0.80	222	<1	0.88	26	410	6	0.09	<5	82	0.21	43	10	30
B380421		3.10	0.76	279	<1	0.60	28	310	16	0.26	<5	101	0.28	60	20	45
B380422		3.29	0.82	288	<1	0.67	34	260	16	0.29	<5	115	0.28	64	20	43
B380423		3.04	0.80	378	<1	0.63	40	500	13	0.35	<5	106	0.32	71	10	56
B380424		1.14	0.27	213	<1	0.32	10	80	10	0.03	5	39	0.14	21	20	17
B380425		1.26	0.37	233	<1	0.47	15	130	9	0.07	<5	65	0.17	29	20	24

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055093

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380426		5.48	0.009	<0.5	6.38	246	530	1.3	<2	0.34	<0.5	11	94	20	2.98	0.02
B380427		4.82	<0.005	<0.5	5.57	393	590	1.1	<2	0.43	<0.5	11	202	16	2.44	0.03
B380428		4.16	<0.005	<0.5	10.00	132	940	2.1	<2	0.40	<0.5	20	112	26	4.30	0.05
B380429		0.04	<0.005													
B380430		0.10	1.470	<0.5	7.13	1245	680	6.4	<2	0.01	<0.5	6	219	39	3.68	0.07
B380431		2.08	<0.005	<0.5	9.74	169	710	2.1	<2	0.23	<0.5	18	70	21	3.18	0.07
B380432		4.92	0.010	<0.5	7.43	228	490	1.5	<2	0.27	<0.5	24	137	34	3.81	0.06
B380433		4.94	0.030	0.6	8.55	511	640	1.8	<2	0.28	0.5	20	123	78	3.90	0.10
B380434		3.42	<0.005	<0.5	8.18	198	590	1.9	<2	0.21	<0.5	11	169	34	3.09	0.03
B380435		1.60	<0.005	<0.5	6.32	67	540	1.4	<2	0.17	<0.5	14	52	37	2.59	0.03
B380436		1.62	<0.005	<0.5	0.15	<5	20	<0.5	<2	20.4	<0.5	1	6	2	0.13	<0.01
B380437		1.44	<0.005	1.8	6.70	113	530	1.5	<2	0.56	<0.5	17	109	36	2.67	0.02
B380438		5.16	0.009	<0.5	8.62	307	610	1.7	<2	1.00	<0.5	20	83	41	3.96	0.01
B380439		5.88	<0.005	<0.5	6.36	163	520	1.4	<2	0.62	<0.5	11	148	24	2.57	0.02
B380440		2.44	0.154	<0.5	7.68	551	500	1.3	<2	2.73	<0.5	27	62	71	5.20	0.01
B380441		1.84	0.006	<0.5	8.35	104	820	2.4	<2	1.20	<0.5	15	86	21	3.67	0.01
B380442		1.32	<0.005	<0.5	8.29	58	910	2.3	<2	0.94	<0.5	17	72	27	4.00	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055093

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380426		2.18	0.65	262	<1	0.76	25	180	9	0.12	6	81	0.29	54	10	51
B380427		1.87	0.55	292	<1	0.30	26	280	10	0.11	5	78	0.25	46	30	30
B380428		3.66	0.95	646	<1	0.15	47	580	12	0.09	<5	103	0.42	87	40	70
B380429																
B380430		2.70	0.35	88	1	0.11	21	320	26	0.02	116	93	0.32	95	10	43
B380431		3.04	0.54	481	<1	0.11	41	410	18	0.08	<5	89	0.36	77	80	68
B380432		1.78	0.52	564	<1	0.06	77	420	9	0.20	12	78	0.40	98	60	58
B380433		2.57	0.62	521	<1	0.09	58	420	14	0.67	14	81	0.39	96	40	60
B380434		2.81	0.63	350	<1	0.21	32	240	10	0.25	<5	78	0.32	78	10	51
B380435		2.26	0.49	270	<1	0.42	24	270	10	0.37	<5	74	0.25	60	10	45
B380436		0.04	11.85	169	<1	0.01	<1	550	4	0.02	<5	114	<0.01	1	<10	5
B380437		2.63	0.68	232	<1	0.54	27	220	11	0.33	<5	102	0.28	63	10	44
B380438		3.29	1.26	374	<1	1.31	45	330	10	0.36	<5	134	0.41	99	10	57
B380439		2.31	0.62	275	<1	0.81	25	210	13	0.22	<5	101	0.25	56	10	38
B380440		2.20	1.48	796	<1	1.46	23	930	16	0.74	<5	220	0.88	194	30	63
B380441		3.02	1.05	407	1	1.25	31	320	12	0.12	<5	125	0.43	89	<10	55
B380442		3.06	1.04	431	<1	1.19	34	320	12	0.14	<5	122	0.44	91	20	66

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 6-JUL-2005
Account: STRGOL

CERTIFICATE VA05055279

Project: Dublin Gulch-1735

P.O. No.:

This report is for 116 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 8-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Au-GRA21	Au 30g FA-GRAV finish	WST-SIM

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381601		2.44	1.015		0.5	6.34	281	1520	2.6	15	2.38	<0.5	9	29	40	2.49
B381602		2.50	0.180		0.5	7.32	233	1540	2.8	5	3.77	<0.5	9	248	60	2.66
B381603		5.40	1.260		<0.5	7.50	207	1560	2.9	14	2.35	<0.5	9	33	46	2.47
B381604		2.06	0.729		<0.5	7.39	70	1620	3.3	15	2.54	<0.5	9	276	32	2.76
B381605		4.24	0.427		1.2	6.49	1310	1000	2.7	6	3.95	0.6	19	25	51	1.78
B381606		6.72	0.164		1.2	7.91	216	1540	3.0	3	2.19	1.0	11	305	54	2.70
B381607		6.22	0.524		<0.5	7.25	223	1620	3.2	6	2.41	<0.5	9	29	50	2.51
B381608		5.80	0.533		0.5	7.72	297	1580	2.9	10	2.35	<0.5	11	294	61	2.73
B381609		<0.02	0.478													
B381610		0.10	4.62		9.6	7.91	<5	480	0.9	<2	2.92	1.3	19	24	134	4.29
B381611		5.44	0.613		0.5	6.64	146	1420	3.0	21	2.62	<0.5	9	24	42	2.34
B381612		4.26	0.320		<0.5	7.60	190	1670	3.3	<2	2.18	<0.5	9	134	46	2.52
B381613		3.16	2.24		3.1	6.80	1235	1040	4.1	83	2.39	1.7	12	28	93	2.87
B381614		2.66	0.639		1.0	7.24	364	1320	3.2	17	2.97	<0.5	10	261	68	2.65
B381615		7.06	0.445		0.9	6.98	299	1230	3.0	14	3.25	0.7	10	28	45	2.15
B381616		2.30	<0.005		<0.5	0.12	<5	20	<0.5	<2	20.9	<0.5	<1	15	5	0.12
B381617		5.48	0.062		<0.5	7.82	512	1480	3.4	<2	2.66	<0.5	10	34	30	2.70
B381618		6.28	0.434		<0.5	7.56	378	1140	2.9	10	3.56	<0.5	10	267	41	2.74
B381619		7.76	0.298		<0.5	7.40	84	1460	3.0	4	1.96	<0.5	8	33	74	2.86
B381620		7.34	0.116		0.7	7.64	75	1440	3.0	<2	1.04	<0.5	8	353	57	3.32
B381621		3.36	0.354		0.9	7.80	170	1180	3.1	2	2.15	0.7	15	38	78	3.30
B381622		2.98	0.226		1.0	6.65	110	1060	2.8	<2	2.05	0.5	12	340	61	2.82
B381623		1.72	0.443		1.2	6.64	138	1510	2.5	4	2.70	<0.5	12	38	91	2.82
B381624		3.66	0.665		0.6	7.59	134	1590	2.7	13	1.70	<0.5	14	377	82	3.41
B381625		3.86	0.129		<0.5	7.35	28	1620	2.9	<2	2.04	<0.5	9	38	33	3.14
B381626		3.18	0.680		0.7	7.04	102	1190	2.7	10	2.02	1.1	10	282	85	2.85
B381627		6.26	0.516		0.6	7.34	93	1520	2.7	10	2.14	<0.5	9	35	87	2.58
B381628		3.42	0.562		0.7	7.65	276	1500	3.0	16	1.48	<0.5	10	285	65	3.22
B381629		<0.02	0.734													
B381630		0.10	0.093		<0.5	6.94	112	590	2.7	<2	0.53	<0.5	61	1230	413	8.76
B381631		4.86	1.260		1.1	7.24	344	1440	3.0	33	1.32	<0.5	13	30	85	2.64
B381632		5.84	1.625		1.3	7.32	218	1350	2.6	47	1.62	0.9	9	396	109	2.77
B381633		4.62	0.242		<0.5	7.61	48	1660	3.0	8	2.03	<0.5	11	37	58	2.93
B381634		6.20	0.674		<0.5	7.72	140	1680	3.3	19	2.72	<0.5	14	232	99	3.21
B381635		6.16	0.394		<0.5	7.95	36	1510	3.8	34	2.75	<0.5	9	46	38	2.87
B381636		2.00	<0.005		<0.5	0.12	<5	20	<0.5	<2	20.1	<0.5	1	24	2	0.12
B381637		6.02	0.082		<0.5	7.58	488	1240	3.5	5	2.75	<0.5	10	47	39	2.81
B381638		7.14	0.253		<0.5	7.67	954	1320	3.2	10	2.51	<0.5	13	265	42	2.94
B381639		5.06	0.200		<0.5	7.15	86	1280	3.3	4	2.65	<0.5	10	253	52	2.97
B381640		1.48	0.075		0.7	7.91	79	1230	3.4	5	3.02	<0.5	9	43	55	2.89

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B381601		<0.01	3.57	0.69	349	3	1.24	21	600	62	0.21	22	377	0.29	37	20
B381602		0.01	3.80	0.78	485	10	1.21	26	650	43	0.30	23	451	0.31	39	20
B381603		0.02	3.71	0.82	279	3	1.55	25	650	30	0.17	8	476	0.31	38	20
B381604		0.01	3.69	0.84	313	2	1.60	35	670	28	0.11	13	470	0.33	40	20
B381605		0.02	3.80	0.41	482	10	0.37	23	620	92	0.64	29	237	0.29	37	30
B381606		0.03	4.10	0.73	331	2	1.28	35	660	46	0.36	28	379	0.31	40	20
B381607		0.02	4.04	0.84	295	7	1.56	23	600	26	0.20	14	464	0.30	36	30
B381608		0.01	3.70	0.86	293	3	1.44	29	680	24	0.25	9	424	0.32	39	20
B381609																
B381610		0.01	2.31	1.41	984	15	1.74	12	920	28	0.69	<5	427	0.40	153	<10
B381611		0.01	3.65	0.84	362	2	1.23	18	570	46	0.16	15	405	0.28	33	20
B381612		0.01	4.08	1.01	336	2	0.82	19	630	47	0.17	18	350	0.30	36	30
B381613		0.02	3.16	0.88	369	5	0.56	15	560	400	0.86	141	348	0.25	37	30
B381614		0.01	3.79	0.68	463	3	0.98	18	620	37	0.58	16	346	0.29	46	10
B381615		0.02	3.63	0.55	501	6	0.74	18	630	95	0.58	23	256	0.29	39	10
B381616		<0.01	0.03	12.05	166	1	0.01	<1	530	10	0.01	<5	112	<0.01	1	<10
B381617		0.02	3.73	1.14	408	3	1.43	17	700	36	0.12	6	493	0.33	49	30
B381618		0.02	3.79	1.15	492	4	1.23	20	590	32	0.22	5	513	0.28	47	30
B381619		0.02	3.86	1.19	309	5	1.00	14	670	32	0.33	14	412	0.31	45	30
B381620		0.01	4.05	0.91	236	3	0.72	22	680	47	0.58	17	250	0.30	45	10
B381621		0.02	3.89	0.80	356	3	0.67	14	720	111	0.72	28	243	0.33	51	30
B381622		0.02	3.46	0.65	339	4	0.66	20	650	95	0.42	18	219	0.30	47	20
B381623		0.01	3.88	0.75	364	4	0.60	14	730	76	0.46	18	285	0.32	49	20
B381624		0.01	3.79	0.95	272	3	0.93	20	740	42	0.50	17	329	0.33	52	10
B381625		<0.01	3.49	1.00	327	2	0.95	16	710	33	0.20	9	369	0.33	49	10
B381626		0.02	3.60	0.97	350	3	0.75	14	670	92	0.41	10	321	0.30	50	20
B381627		0.01	3.98	0.98	297	2	1.12	17	680	36	0.34	10	407	0.31	46	20
B381628		0.01	3.97	0.91	249	7	1.11	23	680	23	1.04	16	358	0.31	46	10
B381629																
B381630		0.03	2.21	0.61	393	10	0.12	501	350	158	0.01	10	51	0.27	94	30
B381631		0.01	3.83	0.71	225	6	0.74	19	620	81	0.68	30	266	0.27	39	20
B381632		0.02	4.27	0.59	287	4	0.42	26	580	213	0.97	78	229	0.25	37	30
B381633		0.01	4.09	1.17	333	18	1.40	20	710	24	0.24	21	505	0.35	47	40
B381634		<0.01	4.15	1.12	318	3	1.75	27	720	28	0.42	7	542	0.36	50	50
B381635		<0.01	3.94	1.18	348	2	1.82	17	720	25	0.20	5	541	0.35	51	30
B381636		<0.01	0.04	11.75	168	<1	0.01	1	520	2	<0.01	<5	110	0.01	2	<10
B381637		<0.01	3.89	1.27	394	3	1.76	18	670	24	0.20	<5	520	0.33	52	10
B381638		0.01	4.19	1.21	391	4	1.44	25	690	49	0.22	12	455	0.34	55	460
B381639		<0.01	3.83	1.28	403	3	1.83	20	700	22	0.19	<5	525	0.35	54	10
B381640		0.01	3.81	1.21	546	2	1.51	18	700	85	0.23	20	472	0.33	55	20

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B381601		110
B381602		86
B381603		61
B381604		57
B381605		154
B381606		191
B381607		47
B381608		72
B381609		
B381610		104
B381611		62
B381612		84
B381613		319
B381614		52
B381615		134
B381616		13
B381617		66
B381618		46
B381619		90
B381620		81
B381621		136
B381622		137
B381623		63
B381624		51
B381625		67
B381626		244
B381627		50
B381628		40
B381629		
B381630		631
B381631		45
B381632		206
B381633		50
B381634		51
B381635		53
B381636		8
B381637		55
B381638		85
B381639		53
B381640		134

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381641		1.58	0.690		3.4	6.82	234	720	2.7	17	4.33	4.0	10	31	52	3.27
B381642		1.72	1.005		4.1	6.79	270	740	2.8	28	3.72	4.5	11	340	72	3.14
B381643		5.32	0.169		<0.5	7.62	33	1330	3.4	5	2.77	<0.5	10	46	43	3.07
B381644		4.36	0.747		0.7	7.86	1075	1240	3.2	17	2.60	<0.5	19	266	80	3.33
B381645		6.14	0.574		<0.5	7.70	674	1510	3.4	19	2.67	<0.5	10	290	62	3.21
B381646		3.08	>10.0	11.85	0.9	7.27	918	1290	3.0	409	1.93	<0.5	12	44	89	3.36
B381647		4.96	0.236		<0.5	7.90	135	1350	3.5	18	2.57	<0.5	9	230	37	2.98
B381648		5.88	0.246		<0.5	7.66	67	1460	3.3	7	2.57	<0.5	11	250	44	3.03
B381649		<0.02	0.342													
B381650		0.10	0.465		2.4	9.73	<5	1120	1.3	<2	1.58	<0.5	6	14	7510	3.42
B381651		2.34	0.953		<0.5	6.97	30	1260	3.4	12	2.43	<0.5	11	90	31	2.67
B381652		5.12	0.131		0.7	7.91	2210	870	2.9	2	1.63	<0.5	10	100	118	4.65
B381653		2.62	1.060		3.3	6.61	>10000	470	2.8	41	2.22	4.5	15	98	238	4.82
B381654		5.96	0.869		0.7	7.89	3550	1180	2.8	20	2.56	<0.5	10	110	31	2.96
B381655		3.36	0.545		<0.5	7.28	264	1460	2.7	18	2.27	<0.5	9	110	59	2.58
B381656		2.38	<0.005		<0.5	0.12	<5	10	<0.5	<2	18.65	<0.5	1	17	2	0.12
B381657		6.56	0.324		<0.5	7.27	97	1640	2.9	8	2.56	<0.5	10	89	51	2.70
B381658		6.18	0.654		<0.5	7.33	125	1600	2.9	16	2.52	<0.5	11	98	67	2.76
B381659		3.84	1.035		<0.5	7.43	447	1600	2.8	14	2.04	<0.5	10	110	78	2.50
B381660		5.66	4.55		1.1	6.98	4450	900	2.6	87	3.25	1.2	21	115	61	2.70
B381661		1.56	0.789		<0.5	6.79	154	1540	2.8	6	2.65	<0.5	11	104	55	2.49
B381662		1.60	1.765		<0.5	7.23	136	1560	2.9	18	2.48	<0.5	10	114	59	2.61
B381663		6.20	0.855		<0.5	6.89	74	1480	2.9	21	2.56	<0.5	8	100	49	2.54
B381664		6.84	0.654		<0.5	7.12	136	1500	2.9	12	2.52	<0.5	8	117	36	2.61
B381665		5.06	0.503		<0.5	7.06	75	1400	2.9	13	2.58	<0.5	9	94	64	2.68
B381666		6.10	0.193		<0.5	6.32	29	1360	2.8	7	2.61	<0.5	8	95	29	2.44
B381667		6.66	0.570		<0.5	6.82	65	1420	2.8	11	2.45	<0.5	9	98	31	2.50
B381668		6.58	0.158		<0.5	7.48	99	1560	3.0	4	2.70	<0.5	10	102	41	2.73
B381669		<0.02	0.206													
B381670		0.10	0.090		<0.5	6.82	104	570	2.7	<2	0.52	<0.5	58	1125	395	8.32
B381671		5.86	0.312		<0.5	7.05	317	1440	2.9	4	2.82	<0.5	16	99	50	2.63
B381672		6.08	1.020		0.5	6.58	52	1420	2.8	12	2.97	<0.5	11	118	38	2.75
B381673		5.68	1.605		<0.5	6.66	121	1310	2.9	26	2.71	<0.5	12	98	33	2.63
B381674		6.08	4.36		<0.5	7.24	966	1460	2.6	65	2.70	<0.5	12	116	55	2.93
B381675		6.14	0.388		<0.5	7.44	106	1470	2.8	11	2.76	<0.5	12	112	47	2.85
B381676		2.20	<0.005		<0.5	0.10	<5	10	<0.5	<2	20.3	<0.5	<1	19	2	0.12
B381677		6.46	1.395		<0.5	8.12	251	1530	2.8	20	2.85	<0.5	13	128	59	2.97
B381678		6.12	3.81		2.0	6.74	41	1350	2.6	73	2.81	<0.5	8	112	25	2.36
B381679		6.58	0.353		0.6	7.57	295	1450	2.9	<2	2.31	<0.5	10	109	68	2.65
B381680		4.54	1.710		0.5	7.12	65	1410	2.8	13	2.57	<0.5	14	122	56	2.86

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method / Analyte / Units / LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B381641		0.07	3.17	1.12	1515	4	0.23	14	560	454	0.55	86	220	0.26	45	30
B381642		0.07	3.36	1.00	1365	3	0.24	20	600	692	0.47	148	205	0.27	46	30
B381643		0.01	3.92	1.26	457	2	1.76	17	720	85	0.30	10	515	0.35	56	10
B381644		<0.01	4.24	1.26	391	7	1.58	23	660	48	0.47	16	484	0.33	52	30
B381645		<0.01	4.00	1.28	362	3	1.69	23	730	23	0.31	9	541	0.36	56	20
B381646		<0.01	4.05	1.04	311	2	1.21	18	630	42	0.66	20	370	0.29	49	100
B381647		<0.01	4.17	1.32	391	3	1.74	22	720	32	0.19	<5	511	0.34	54	40
B381648		<0.01	3.91	1.24	364	3	1.75	22	690	23	0.21	7	521	0.34	54	50
B381649																
B381650		0.02	3.81	1.20	498	3	3.63	10	1920	12	0.24	<5	712	0.35	179	<10
B381651		0.01	3.68	1.16	360	2	1.50	24	640	24	0.16	8	460	0.33	53	40
B381652		0.01	4.02	1.00	408	1	0.40	21	700	61	2.08	22	189	0.29	55	50
B381653		0.08	3.00	0.81	674	3	0.04	15	590	389	2.52	186	130	0.23	41	50
B381654		0.01	3.85	0.90	406	8	1.31	20	690	71	0.43	32	337	0.33	49	30
B381655		0.01	3.75	0.95	311	3	1.20	19	640	50	0.36	16	370	0.29	44	40
B381656		<0.01	0.03	11.00	144	<1	0.01	<1	450	<2	0.01	<5	110	0.01	2	<10
B381657		0.01	3.64	1.20	326	2	1.83	20	690	20	0.21	5	571	0.34	48	40
B381658		<0.01	3.66	1.08	263	7	1.83	18	680	19	0.28	<5	564	0.33	48	50
B381659		0.01	3.66	0.97	215	2	1.50	18	650	18	0.34	6	486	0.32	45	40
B381660		0.01	3.34	0.62	515	4	0.53	17	590	87	0.67	34	239	0.27	41	30
B381661		0.01	3.96	0.90	282	5	1.55	19	650	21	0.24	13	487	0.32	44	20
B381662		0.01	4.08	0.97	267	4	1.56	19	650	20	0.25	10	485	0.33	45	30
B381663		<0.01	3.53	0.97	274	9	1.76	18	640	17	0.22	<5	512	0.32	46	10
B381664		<0.01	3.63	1.05	325	13	1.82	20	650	21	0.18	<5	539	0.32	48	40
B381665		<0.01	3.59	1.11	310	6	1.85	20	630	22	0.29	<5	517	0.32	49	140
B381666		<0.01	3.42	0.93	329	2	1.97	17	610	26	0.13	5	494	0.30	45	20
B381667		<0.01	3.53	1.00	311	2	1.78	16	630	22	0.15	<5	501	0.31	48	10
B381668		<0.01	3.74	1.02	304	2	1.76	20	680	22	0.19	6	525	0.34	51	20
B381669																
B381670		0.03	2.22	0.58	373	9	0.12	470	340	142	0.02	14	51	0.24	91	30
B381671		<0.01	3.63	1.00	336	11	1.79	18	650	23	0.20	<5	507	0.32	49	30
B381672		<0.01	3.31	1.09	371	3	1.68	18	660	25	0.16	5	520	0.30	53	50
B381673		<0.01	3.75	1.06	337	2	1.62	13	610	31	0.16	<5	480	0.28	50	90
B381674		<0.01	3.79	1.16	311	3	1.60	16	680	25	0.32	7	513	0.30	54	30
B381675		0.01	3.78	1.14	336	6	1.93	12	700	26	0.23	<5	541	0.30	55	30
B381676		<0.01	0.03	11.65	158	<1	0.01	2	530	5	0.01	<5	113	<0.01	1	<10
B381677		<0.01	4.19	1.23	317	2	1.76	13	680	30	0.25	<5	553	0.30	54	40
B381678		<0.01	3.53	0.83	313	1	1.76	18	620	29	0.13	<5	487	0.26	39	10
B381679		0.01	3.72	0.90	260	3	1.47	20	670	35	0.39	5	428	0.30	42	50
B381680		<0.01	3.40	1.17	290	1	1.74	23	660	25	0.19	<5	502	0.32	51	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B381641		702
B381642		770
B381643		83
B381644		70
B381645		51
B381646		85
B381647		55
B381648		53
B381649		
B381650		64
B381651		53
B381652		120
B381653		773
B381654		98
B381655		59
B381656		7
B381657		38
B381658		29
B381659		26
B381660		272
B381661		37
B381662		32
B381663		34
B381664		45
B381665		42
B381666		50
B381667		49
B381668		48
B381669		
B381670		603
B381671		49
B381672		44
B381673		43
B381674		32
B381675		37
B381676		7
B381677		41
B381678		45
B381679		111
B381680		36

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381681		3.02	1.590		<0.5	7.22	39	1340	3.2	26	2.71	<0.5	13	118	37	3.02
B381682		2.72	1.225		<0.5	6.65	33	1270	2.9	15	2.65	<0.5	14	119	30	2.90
B381683		5.66	1.060		0.6	7.64	80	1490	3.3	7	2.57	<0.5	14	101	66	2.92
B381684		3.88	0.018		<0.5	4.12	134	590	1.0	<2	0.84	<0.5	9	158	14	2.80
B381685		2.98	0.052		0.7	3.30	590	370	0.9	<2	0.76	0.5	5	164	15	1.82
B381686		1.34	0.021		<0.5	7.21	347	1140	2.0	<2	0.48	0.8	11	136	15	3.68
B381687		3.82	0.019		<0.5	5.41	276	710	1.3	<2	0.35	<0.5	8	160	16	2.19
B381688		1.94	0.005		<0.5	9.34	127	1240	2.2	<2	0.21	<0.5	11	140	16	1.78
B381689		<0.02	0.005													
B381690		0.10	0.094		<0.5	6.96	123	610	2.8	<2	0.52	<0.5	67	1240	420	8.75
B381691		0.86	0.006		<0.5	6.39	305	760	1.6	<2	0.20	2.6	9	138	24	2.65
B381692		1.86	0.053		<0.5	4.08	927	330	1.1	<2	0.10	3.3	5	154	13	1.85
B381693		2.42	0.151		1.0	3.92	1330	400	1.0	<2	0.63	6.5	5	126	17	2.49
B381694		6.00	1.685		4.7	8.46	733	750	2.4	49	0.82	7.0	21	147	42	2.42
B381695		5.72	0.053		0.7	6.38	579	650	1.9	<2	0.11	3.5	12	134	33	2.50
B381696		2.02	<0.005		<0.5	0.17	9	20	<0.5	<2	19.90	<0.5	<1	8	2	0.13
B381697		3.52	0.064		0.7	6.81	416	680	1.7	<2	0.29	2.7	13	167	30	3.37
B381698		1.96	0.051		<0.5	6.64	2200	970	1.6	<2	0.29	12.5	40	124	49	5.83
B381699		6.56	0.715		<0.5	7.20	495	850	1.8	<2	0.39	0.9	16	140	26	3.40
B381700		6.00	0.254		<0.5	7.14	956	760	1.7	<2	0.71	0.6	13	147	28	3.55
B381701		3.16	0.349		<0.5	6.24	718	710	1.6	11	0.79	0.6	16	140	32	2.86
B381702		3.04	0.185		<0.5	6.34	616	700	1.7	10	0.75	0.6	12	148	30	2.87
B381703		5.50	0.060		<0.5	8.10	285	1170	2.1	<2	0.73	<0.5	13	124	24	2.98
B381704		3.72	0.019		1.1	7.01	435	840	1.7	<2	0.87	<0.5	11	168	23	2.98
B381705		5.64	0.005		<0.5	9.26	87	1210	2.4	<2	0.33	<0.5	18	140	28	4.12
B381706		5.76	0.084		<0.5	5.11	386	690	1.6	<2	1.17	<0.5	11	168	34	2.51
B381707		5.24	0.009		<0.5	7.14	270	760	1.7	<2	1.04	<0.5	11	142	31	3.07
B381708		2.20	<0.005		<0.5	8.54	178	930	2.2	<2	1.17	<0.5	15	147	23	3.45
B381709		<0.02	<0.005													
B381710		0.12	0.931		2.5	7.44	18	470	0.7	<2	1.86	0.9	27	97	2040	5.26
B381711		5.34	0.006		<0.5	8.41	60	870	1.9	<2	1.52	<0.5	14	134	31	3.62
B381712		6.12	3.60		<0.5	8.37	229	1040	2.1	196	0.81	<0.5	14	148	25	3.53
B381713		6.34	1.365		<0.5	8.04	584	990	2.0	25	1.42	<0.5	15	138	45	3.34
B381714		5.50	0.024		<0.5	6.18	284	650	1.7	<2	1.13	<0.5	10	154	23	2.36
B381715		6.18	0.040		<0.5	4.72	385	470	1.1	<2	1.09	<0.5	7	136	18	2.02
B381716		2.44	<0.005		<0.5	0.12	11	10	<0.5	<2	20.1	<0.5	1	9	3	0.12

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method / Analyte / Units / LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B381681		<0.01	3.55	1.29	333	2	1.84	22	690	23	0.13	<5	517	0.33	57	10
B381682		<0.01	3.58	1.26	326	1	1.81	23	680	23	0.12	<5	491	0.32	56	20
B381683		<0.01	4.23	1.20	273	3	1.88	21	730	21	0.26	<5	535	0.35	54	40
B381684		0.01	1.88	0.27	558	2	0.43	21	90	14	0.04	20	61	0.18	42	10
B381685		0.04	1.42	0.16	534	3	0.08	13	90	134	0.04	39	23	0.13	30	10
B381686		0.04	3.51	0.78	262	1	1.09	23	230	34	0.01	20	169	0.32	61	10
B381687		0.01	2.43	0.38	212	5	0.43	19	130	69	0.01	19	58	0.20	46	10
B381688		0.04	4.42	0.33	112	1	0.61	20	210	13	0.03	12	117	0.33	88	<10
B381689																
B381690		0.03	2.32	0.58	387	9	0.12	535	340	150	0.02	16	53	0.26	96	40
B381691		0.05	2.99	0.41	177	2	0.69	21	440	25	0.02	38	66	0.26	60	10
B381692		0.03	1.78	0.12	448	6	0.15	17	160	46	<0.01	124	26	0.14	26	10
B381693		0.19	1.82	0.16	1295	6	0.15	7	280	1995	0.03	720	27	0.15	31	10
B381694		0.02	3.49	0.31	1965	7	0.06	34	280	130	0.04	82	34	0.35	81	20
B381695		0.05	2.71	0.27	704	4	0.15	25	140	107	0.03	76	29	0.25	56	20
B381696		<0.01	0.05	11.35	171	<1	0.01	1	560	5	0.01	<5	112	<0.01	1	<10
B381697		0.04	2.66	0.50	439	2	0.60	26	170	17	0.04	43	75	0.31	61	10
B381698		0.04	2.70	0.61	4610	16	0.65	66	210	35	0.12	78	97	0.31	61	30
B381699		0.02	2.99	0.71	340	2	0.84	26	200	12	0.02	7	102	0.34	69	10
B381700		0.02	3.04	0.79	339	1	0.85	24	260	14	0.03	12	114	0.35	65	10
B381701		0.02	2.82	0.50	244	2	0.63	26	220	11	0.09	36	114	0.27	55	30
B381702		0.02	2.70	0.51	245	1	0.65	26	270	11	0.05	29	111	0.28	55	40
B381703		0.02	3.79	0.73	198	3	0.76	28	460	22	0.02	9	181	0.35	72	10
B381704		0.02	3.10	0.56	224	5	0.63	25	300	17	0.02	23	105	0.32	64	40
B381705		0.01	4.33	0.85	166	1	1.05	41	520	18	0.03	<5	128	0.42	96	10
B381706		0.01	1.99	0.54	288	1	0.68	19	170	14	0.04	5	132	0.22	42	130
B381707		0.01	2.83	0.78	327	1	0.91	23	310	17	0.03	5	138	0.32	61	10
B381708		0.02	3.28	0.85	293	1	0.77	33	260	15	0.01	<5	141	0.39	78	20
B381709																
B381710		0.04	1.75	1.34	432	3	3.09	51	690	31	0.62	<5	217	0.30	92	10
B381711		0.01	2.97	0.93	416	<1	0.91	30	310	9	0.19	<5	170	0.41	78	10
B381712		<0.01	4.06	0.82	257	4	1.02	32	530	18	0.06	5	136	0.41	85	10
B381713		0.01	3.10	0.88	396	<1	1.05	32	250	14	0.06	<5	182	0.37	73	10
B381714		0.01	2.29	0.56	271	1	0.84	19	180	12	0.05	<5	119	0.30	56	20
B381715		0.01	1.78	0.45	209	1	0.83	13	170	8	0.02	<5	90	0.21	41	20
B381716		<0.01	0.03	11.50	163	<1	0.01	<1	470	2	0.02	<5	108	<0.01	1	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 16-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05055279

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B381681		36
B381682		34
B381683		30
B381684		76
B381685		197
B381686		363
B381687		118
B381688		65
B381689		
B381690		663
B381691		489
B381692		346
B381693		841
B381694		1155
B381695		682
B381696		14
B381697		656
B381698		1750
B381699		351
B381700		203
B381701		194
B381702		192
B381703		133
B381704		169
B381705		78
B381706		89
B381707		96
B381708		67
B381709		
B381710		212
B381711		57
B381712		69
B381713		67
B381714		39
B381715		22
B381716		8

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da .6-JUL-2005
Account: STRGOL

CERTIFICATE VA05058631

Project: Dublin Gulch-1735

P.O. No.:

This report is for 55 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058631

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380467		3.84	0.057	<0.5	7.79	1525	1350	4.2	6	1.91	<0.5	2	68	104	1.79	0.01
B380468		5.24	0.382	<0.5	7.46	>10000	1230	2.9	47	1.79	<0.5	38	106	40	3.04	0.01
B380469		0.04	0.354													
B380470		0.10	3.39	0.6	7.21	15	2080	2.8	<2	4.77	<0.5	18	118	86	5.12	0.01
B380471		5.84	0.082	<0.5	7.75	2550	1240	3.0	12	2.22	<0.5	7	100	64	2.46	<0.01
B380472		5.38	0.070	<0.5	7.25	2540	1350	3.3	6	1.92	<0.5	8	84	64	1.96	<0.01
B380478		4.18	0.143	<0.5	7.63	4850	1400	3.2	38	1.95	<0.5	8	90	116	2.48	0.01
B380479		5.42	0.102	<0.5	7.65	4410	1400	3.2	11	2.09	<0.5	7	102	111	2.35	0.01
B380480		3.74	0.133	<0.5	7.34	3500	1300	3.3	23	2.20	<0.5	5	93	138	2.30	0.01
B380481		2.24	0.466	<0.5	7.70	5180	1330	3.4	70	1.86	<0.5	5	95	119	2.35	<0.01
B380482		2.08	0.543	<0.5	7.83	7340	1330	3.4	76	2.17	<0.5	6	97	106	2.51	0.01
B380483		1.28	0.740	<0.5	7.44	>10000	850	1.5	130	1.26	<0.5	14	83	14	3.37	<0.01
B380484		6.00	0.737	<0.5	7.71	>10000	1430	1.8	89	1.22	<0.5	12	86	54	2.76	0.01
B380485		4.74	0.697	<0.5	7.67	>10000	1380	2.6	81	1.68	<0.5	7	77	77	2.75	0.01
B380486		1.50	0.096	<0.5	7.48	2190	1120	2.9	8	2.13	<0.5	6	96	63	2.54	<0.01
B380492		6.50	0.172	<0.5	7.05	6590	1460	2.7	24	1.83	<0.5	13	88	61	2.49	0.01
B380493		5.28	0.068	<0.5	7.73	3050	1380	3.1	9	2.04	<0.5	7	88	50	2.29	0.01
B380494		7.04	0.156	<0.5	7.89	2350	1460	3.2	10	1.94	<0.5	6	85	44	2.56	<0.01
B380495		2.86	0.091	<0.5	7.48	2660	1480	2.9	9	1.82	<0.5	6	90	67	2.31	0.01
B380496		1.84	<0.005	<0.5	0.14	15	20	<0.5	<2	18.60	<0.5	<1	7	2	0.12	<0.01
B380497		2.66	0.143	<0.5	7.70	4920	1340	2.8	17	1.94	<0.5	9	90	65	2.93	<0.01
B380498		2.08	0.122	<0.5	7.26	3790	1490	2.8	16	2.84	<0.5	6	72	82	1.96	0.01
B380499		6.12	0.130	<0.5	7.47	3700	1500	2.9	15	2.05	<0.5	8	92	98	2.41	<0.01
B380500		5.04	0.224	<0.5	7.78	4950	1500	3.2	69	1.85	<0.5	8	89	98	2.46	<0.01
B380526		6.32	0.174	<0.5	7.64	5110	1450	2.9	16	2.06	<0.5	9	88	73	2.26	<0.01
B380527		5.72	0.131	<0.5	7.50	3350	1360	3.1	9	1.96	<0.5	7	88	57	2.11	<0.01
B380528		6.54	0.157	<0.5	7.61	3040	1440	3.0	12	2.18	<0.5	7	82	88	2.16	<0.01
B380529		0.04	0.155													
B380530		0.10	0.106	<0.5	7.01	112	590	2.6	2	0.52	<0.5	55	1150	401	8.47	0.03
B380540		5.64	0.123	<0.5	7.14	2230	1380	3.2	7	2.12	<0.5	7	84	28	2.25	<0.01
B380541		2.64	0.130	<0.5	8.15	3740	1600	3.3	13	2.10	<0.5	8	91	61	2.61	<0.01
B380542		2.84	0.150	<0.5	7.77	3180	1510	3.3	8	2.11	<0.5	7	82	59	2.33	<0.01
B380543		4.24	0.133	<0.5	7.43	3810	1420	3.1	10	2.09	<0.5	8	87	40	2.11	<0.01
B380553		5.94	0.123	<0.5	7.74	3390	1500	3.1	9	2.33	<0.5	7	78	42	2.23	<0.01
B380554		5.88	0.178	<0.5	7.22	4330	1350	2.7	13	2.28	<0.5	8	92	32	2.56	<0.01
B380555		5.80	0.124	<0.5	7.43	3410	1460	3.0	10	2.32	<0.5	8	94	48	2.45	<0.01
B380556		1.70	0.009	<0.5	0.14	14	20	<0.5	<2	19.90	<0.5	<1	9	2	0.13	<0.01
B380557		5.80	0.169	<0.5	6.92	3850	1420	2.8	18	2.63	<0.5	11	94	45	2.37	<0.01
B380558		4.90	0.157	<0.5	6.91	2980	1300	2.8	13	2.98	<0.5	9	100	50	2.33	<0.01
B380559		5.60	0.091	<0.5	6.76	1540	1280	2.8	7	2.79	<0.5	7	99	48	2.34	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058631

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B380467		4.80	0.73	108	2	1.45	9	490	14	0.47	<5	418	0.17	35	10	15
B380468		4.82	0.76	149	<1	1.34	14	570	21	0.90	7	492	0.25	39	20	22
B380469																
B380470		3.00	2.95	1060	12	2.42	54	2280	29	0.32	<5	1645	0.32	140	<10	79
B380471		4.24	0.84	202	2	1.65	12	580	26	0.42	<5	506	0.28	43	10	30
B380472		4.26	0.60	118	2	1.58	13	480	21	0.46	<5	419	0.22	29	10	20
B380478		4.55	0.79	112	2	1.27	15	600	19	0.64	<5	398	0.27	41	20	17
B380479		4.69	0.83	115	2	1.51	15	590	18	0.60	5	476	0.27	41	20	14
B380480		4.96	0.79	123	1	1.43	14	590	17	0.62	<5	483	0.28	42	30	13
B380481		5.17	0.74	95	<1	1.35	13	570	17	0.48	5	469	0.27	41	10	13
B380482		5.31	0.86	105	1	1.32	13	580	18	0.55	5	475	0.27	41	30	13
B380483		6.63	0.54	93	1	0.69	9	550	19	1.48	21	356	0.23	36	30	9
B380484		6.08	0.56	87	1	0.82	12	560	15	1.07	12	392	0.26	38	30	10
B380485		4.90	0.82	117	1	1.10	13	590	16	0.87	10	431	0.26	41	80	12
B380486		3.52	0.94	245	1	1.80	14	560	17	0.36	<5	471	0.29	57	10	24
B380492		3.90	0.77	127	2	1.21	17	560	16	0.63	9	374	0.27	35	10	19
B380493		4.12	0.84	159	1	1.41	13	550	25	0.34	<5	413	0.25	38	10	29
B380494		4.04	0.99	189	1	1.54	16	600	28	0.32	<5	445	0.28	41	10	31
B380495		3.74	0.91	139	2	1.35	20	590	21	0.32	<5	407	0.28	37	10	23
B380496		0.04	10.85	150	<1	0.02	3	480	6	0.01	<5	126	0.01	2	<10	7
B380497		4.22	0.95	141	1	1.36	22	610	20	1.00	7	448	0.29	36	10	16
B380498		4.41	0.79	132	2	1.12	15	600	19	0.48	5	418	0.28	37	10	13
B380499		4.25	0.92	112	2	1.25	19	580	18	0.54	<5	439	0.28	37	10	14
B380500		4.31	0.87	102	2	1.38	18	610	19	0.62	<5	451	0.28	37	10	13
B380526		4.51	0.75	112	<1	1.38	21	560	22	0.48	<5	429	0.28	35	10	17
B380527		4.43	0.77	143	1	1.48	21	560	26	0.32	<5	432	0.28	35	10	26
B380528		4.34	0.79	129	1	1.52	20	560	24	0.38	<5	435	0.28	36	<10	19
B380529																
B380530		2.20	0.58	375	8	0.13	456	350	146	0.02	6	52	0.19	91	30	593
B380540		3.87	0.84	217	1	1.49	20	560	29	0.23	<5	463	0.27	34	10	40
B380541		4.17	0.92	172	1	1.60	25	620	22	0.39	<5	481	0.31	40	10	23
B380542		4.04	0.83	158	2	1.51	21	620	20	0.34	<5	457	0.30	37	10	21
B380543		4.44	0.74	142	2	1.40	19	570	25	0.36	<5	437	0.28	38	30	21
B380553		4.21	0.88	166	<1	1.69	17	620	15	0.34	<5	534	0.29	41	<10	18
B380554		3.77	0.92	201	2	1.58	16	600	13	0.36	<5	508	0.28	51	10	28
B380555		4.57	0.95	188	1	1.62	16	630	17	0.32	<5	514	0.30	49	10	22
B380556		0.03	11.40	151	<1	0.02	3	470	3	0.02	<5	114	0.01	2	<10	7
B380557		4.50	0.96	207	2	1.63	15	600	15	0.34	<5	498	0.29	47	20	20
B380558		4.33	1.11	216	2	1.55	13	570	17	0.30	<5	494	0.27	47	10	20
B380559		3.88	1.01	251	1	1.68	13	580	16	0.28	<5	494	0.28	51	<10	21

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058631

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380571		5.56	0.168	<0.5	7.31	2060	1410	3.0	22	2.46	<0.5	8	108	83	2.65	0.01
B380572		2.62	0.104	<0.5	7.34	2650	1660	3.1	9	2.12	<0.5	8	90	127	2.80	0.01
B380573		2.90	0.200	<0.5	7.30	1230	1360	2.8	23	2.40	<0.5	7	96	117	2.27	0.01
B380574		6.14	0.149	<0.5	7.04	3010	1180	2.8	23	3.48	<0.5	10	94	92	2.72	0.01
B380580		6.60	0.049	<0.5	7.18	1790	1500	3.1	4	2.36	<0.5	7	100	70	2.45	<0.01
B380581		3.60	0.046	<0.5	7.52	1240	1630	3.3	7	2.11	<0.5	7	88	65	2.41	<0.01
B380582		3.00	0.060	<0.5	7.75	1565	1630	3.2	6	2.39	<0.5	7	93	58	2.52	0.01
B380583		6.66	0.090	1.1	7.05	1960	1240	2.7	9	3.07	1.5	7	83	50	2.06	0.04
B380584		7.02	0.056	1.0	7.54	1260	1390	3.2	7	2.56	<0.5	7	100	69	2.19	0.01
B380585		6.08	0.059	<0.5	7.47	2340	1160	3.1	11	2.58	<0.5	7	89	76	2.23	0.01
B380586		6.04	0.046	<0.5	7.49	1440	1520	3.2	8	2.39	<0.5	7	95	78	2.07	0.01
B380607		6.70	0.027	<0.5	8.08	648	1430	3.4	4	2.67	<0.5	9	89	53	2.59	<0.01
B380608		5.18	0.026	<0.5	7.46	396	1340	3.5	<2	2.19	<0.5	7	89	57	2.22	<0.01
B380609		0.10	0.028													
B380610		0.04	3.00	0.7	7.03	<5	2030	3.1	<2	4.65	<0.5	23	135	95	5.02	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 26-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058631

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380571		4.01	1.06	238	<1	1.19	18	700	20	0.39	5	376	0.31	53	10	25
B380572		4.16	1.17	179	1	1.49	17	680	16	0.56	<5	472	0.33	49	10	23
B380573		4.20	0.69	175	1	1.06	19	670	16	0.60	9	313	0.31	48	10	19
B380574		3.87	0.88	334	1	0.90	17	590	16	0.57	10	341	0.28	51	20	22
B380580		3.79	0.82	203	1	1.60	19	600	20	0.42	<5	477	0.30	41	<10	21
B380581		4.01	0.84	183	1	1.64	22	620	17	0.35	<5	486	0.31	40	10	21
B380582		3.97	0.90	226	1	1.52	21	610	17	0.36	<5	478	0.31	40	10	22
B380583		3.75	0.62	456	1	0.75	19	570	95	0.41	10	304	0.28	37	10	265
B380584		4.08	0.62	417	1	1.11	21	600	102	0.47	8	354	0.28	37	10	78
B380585		3.93	0.56	543	<1	0.73	19	610	22	0.46	9	291	0.27	40	10	17
B380586		4.41	0.67	172	<1	1.35	20	610	20	0.38	<5	420	0.30	38	10	22
B380607		3.90	1.14	285	1	1.82	13	660	23	0.24	<5	551	0.31	49	10	32
B380608		3.88	0.94	214	1	1.77	17	600	17	0.26	<5	496	0.29	43	<10	26
B380609																
B380610		3.30	2.89	1035	13	2.36	63	2250	29	0.30	<5	1595	0.35	158	<10	88

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 8-JUL-2005
Account: STRGOL

CERTIFICATE VA05058632

Project: Dublin Gulch-1735

P.O. No.:

This report is for 71 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Au-GRA21	Au 30g FA-GRAV finish	WST-SIM

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B381717		5.70	0.082				<0.5	6.10	243	610	1.6	7	1.06	<0.5	8	96
B381718		3.66	0.034				<0.5	8.34	208	870	2.1	<2	1.41	<0.5	11	77
B381719		3.48	0.278				<0.5	7.47	353	900	1.8	14	1.17	<0.5	8	73
B381720		3.26	0.098				<0.5	7.28	346	800	1.9	5	1.06	<0.5	8	90
B381721		0.30	0.035				<0.5	6.59	267	700	1.8	2	0.90	<0.5	9	148
B381722		0.36	1.845				<0.5	8.91	540	960	2.6	49	0.70	<0.5	20	106
B381723		3.06	0.051				<0.5	7.37	333	860	1.8	2	1.08	<0.5	12	79
B381724		4.60	0.252				<0.5	3.32	589	350	0.7	18	0.61	<0.5	4	54
B381741		2.64	0.054				<0.5	8.27	268	1470	2.5	5	2.76	<0.5	12	96
B381742		2.42	0.342				<0.5	7.80	489	1390	2.4	8	2.73	<0.5	13	92
B381743		5.34	0.010				<0.5	8.50	77	1480	2.5	2	2.81	<0.5	13	88
B381744		6.08	0.047				<0.5	8.21	92	1450	2.4	3	2.88	<0.5	13	96
B381745		5.80	0.075				<0.5	7.84	79	1410	2.3	14	2.64	<0.5	13	96
B381746		3.98	0.061				<0.5	8.65	351	1480	2.5	11	2.87	<0.5	12	115
B381747		2.00	0.204				<0.5	7.17	869	1140	2.1	15	2.45	<0.5	13	88
B381748		6.46	0.070				<0.5	8.29	812	1450	2.5	2	2.79	<0.5	13	91
B381749		0.04	0.065													
B381750		0.10	0.094				<0.5	7.02	117	590	2.7	<2	0.53	<0.5	57	1205
B381751		5.92	0.009				<0.5	8.39	66	1450	2.5	<2	2.76	<0.5	12	98
B381752		5.30	0.070				<0.5	7.83	396	1380	2.5	3	2.62	<0.5	12	107
B381753		6.08	0.100				<0.5	8.18	302	1430	2.7	3	2.74	<0.5	12	83
B381754		5.82	0.148				<0.5	8.06	562	1440	2.6	15	2.65	<0.5	13	100
B381755		4.62	0.102				<0.5	8.15	205	1450	2.5	6	2.47	<0.5	12	83
B381756		0.36	<0.005				<0.5	0.19	<5	20	<0.5	<2	20.2	<0.5	<1	5
B381757		5.28	0.073				<0.5	8.33	114	1530	2.5	2	2.90	<0.5	13	88
B381758		3.16	0.098				<0.5	8.05	710	1480	2.5	3	2.78	<0.5	12	71
B381759		2.66	1.210				<0.5	5.54	1360	980	1.7	52	1.84	<0.5	11	93
B381760		4.88	0.046				<0.5	8.38	242	1410	2.6	5	2.74	<0.5	12	89
B381761		2.62	0.081				<0.5	7.68	316	1430	2.4	14	2.65	<0.5	13	65
B381762		2.82	0.066				<0.5	8.35	491	1390	2.7	4	2.89	<0.5	13	86
B381763		5.14	0.154				<0.5	7.41	1150	1320	2.5	14	2.31	<0.5	12	63
B381774		5.60	0.169				<0.5	8.01	108	1390	2.8	19	2.51	<0.5	8	66
B381775		5.26	0.450				<0.5	7.99	1200	1570	2.8	21	2.66	<0.5	12	42
B381776		0.22	<0.005				<0.5	0.11	5	20	<0.5	<2	19.70	<0.5	<1	3
B381777		2.98	0.702				<0.5	6.96	2470	1260	2.6	38	2.20	<0.5	13	41
B381778		2.88	0.356				<0.5	8.01	1320	1510	3.0	26	2.57	<0.5	14	68
B381779		1.44	0.968				<0.5	7.89	2230	1440	2.8	39	2.06	<0.5	13	40
B381780		4.46	0.528	0.875	0.893		<0.5	7.49	1790	1400	2.8	19	2.07	<0.5	17	70
B381785		5.24	0.212				<0.5	7.30	385	1420	2.8	<2	2.61	<0.5	12	47
B381786		3.38	1.915				0.5	6.88	1585	1380	2.4	78	1.92	<0.5	24	51

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B381717		22	2.68	0.01	2.50	0.68	310	1	0.81	22	180	8	0.03	<5	108	0.28
B381718		23	2.39	0.01	3.52	0.63	279	1	0.81	28	420	9	0.03	<5	164	0.33
B381719		15	1.50	0.01	3.58	0.44	207	1	0.69	16	480	4	0.02	<5	127	0.25
B381720		26	2.79	0.01	2.99	0.73	246	1	0.81	26	320	3	0.03	<5	126	0.32
B381721		15	2.89	0.01	3.31	0.62	218	1	0.88	26	170	7	0.01	<5	94	0.28
B381722		20	3.33	0.01	4.29	0.83	216	1	1.07	39	200	3	0.05	5	110	0.40
B381723		17	2.91	0.01	3.39	0.70	281	1	0.85	29	330	7	0.01	<5	99	0.34
B381724		10	1.21	<0.01	1.35	0.18	135	<1	0.42	10	100	3	0.01	<5	51	0.15
B381741		25	3.60	<0.01	2.99	1.56	422	3	1.69	40	820	31	0.05	<5	480	0.45
B381742		20	3.44	<0.01	2.81	1.48	405	2	1.61	39	780	22	0.06	<5	456	0.42
B381743		23	3.81	<0.01	2.96	1.62	455	2	1.74	39	830	27	0.06	<5	495	0.46
B381744		17	3.70	<0.01	2.83	1.55	446	1	1.74	42	850	21	0.05	<5	484	0.45
B381745		21	3.62	0.01	2.92	1.52	445	3	1.69	42	820	22	0.05	<5	478	0.45
B381746		16	3.85	<0.01	3.05	1.63	439	2	1.71	44	900	22	0.05	<5	490	0.46
B381747		16	3.11	<0.01	2.62	1.40	318	2	1.27	36	710	17	0.12	<5	336	0.37
B381748		17	3.74	<0.01	2.86	1.59	432	3	1.74	43	840	24	0.11	<5	490	0.46
B381749																
B381750		407	8.47	0.03	2.17	0.60	376	9	0.13	482	360	146	0.02	12	53	0.23
B381751		17	3.75	<0.01	2.79	1.57	432	1	1.68	40	810	21	0.05	<5	480	0.45
B381752		17	3.52	<0.01	3.02	1.47	394	3	1.63	41	770	21	0.07	<5	458	0.43
B381753		19	3.44	<0.01	3.03	1.50	334	3	1.65	39	790	17	0.08	<5	472	0.41
B381754		27	3.53	<0.01	3.31	1.52	336	3	1.61	39	790	19	0.12	<5	467	0.44
B381755		34	3.48	<0.01	3.00	1.49	338	1	1.58	41	780	19	0.16	<5	445	0.41
B381756		2	0.15	<0.01	0.06	11.55	184	<1	0.02	5	440	<2	0.01	<5	114	0.01
B381757		29	3.81	0.01	3.12	1.64	470	2	1.75	40	900	25	0.13	<5	515	0.45
B381758		22	3.37	<0.01	3.41	1.53	358	1	1.58	38	800	20	0.13	<5	469	0.43
B381759		11	2.08	<0.01	2.51	0.93	192	4	0.98	29	530	11	0.12	<5	284	0.27
B381760		17	3.43	0.01	2.74	1.57	391	3	1.77	38	810	16	0.07	<5	478	0.43
B381761		22	3.27	0.01	2.87	1.46	351	3	1.54	41	800	17	0.11	<5	441	0.41
B381762		22	3.43	0.01	2.81	1.55	363	3	1.60	40	820	17	0.12	<5	448	0.42
B381763		29	3.09	0.01	3.01	1.36	337	8	1.45	36	710	20	0.16	<5	414	0.37
B381774		55	2.87	<0.01	3.41	1.19	318	1	1.69	24	650	20	0.21	<5	531	0.31
B381775		82	2.80	<0.01	3.54	1.29	230	1	1.62	17	730	16	0.39	<5	558	0.30
B381776		1	0.11	<0.01	0.03	11.55	118	<1	0.01	2	440	2	0.01	<5	112	<0.01
B381777		126	2.45	<0.01	3.33	1.17	134	2	1.33	17	640	14	0.43	<5	428	0.27
B381778		132	3.19	0.01	3.66	1.36	252	1	1.71	24	760	14	0.57	<5	572	0.33
B381779		115	2.67	<0.01	4.41	1.18	186	3	1.37	19	680	21	0.39	<5	485	0.29
B381780		174	2.70	0.01	3.82	1.09	212	1	1.33	26	620	21	0.64	<5	465	0.27
B381785		40	2.82	0.01	3.22	1.12	309	2	1.48	21	680	19	0.20	7	460	0.35
B381786		127	2.85	<0.01	3.83	0.70	174	2	1.22	28	530	23	1.02	<5	415	0.24

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	V	W	Zn
	Units	ppm	ppm	ppm
	LOR	1	10	2
B381717		53	20	40
B381718		72	30	34
B381719		63	10	21
B381720		66	20	49
B381721		61	20	47
B381722		87	10	64
B381723		70	30	45
B381724		24	20	12
B381741		115	20	107
B381742		105	10	94
B381743		112	<10	104
B381744		110	<10	100
B381745		109	<10	96
B381746		117	<10	88
B381747		97	480	68
B381748		114	10	89
B381749				
B381750		91	30	613
B381751		110	<10	91
B381752		108	40	82
B381753		99	<10	67
B381754		109	10	70
B381755		101	10	76
B381756		3	<10	7
B381757		110	10	94
B381758		106	40	75
B381759		66	830	40
B381760		103	10	96
B381761		98	10	94
B381762		101	<10	99
B381763		90	10	74
B381774		65	<10	57
B381775		53	30	29
B381776		2	<10	6
B381777		52	30	22
B381778		63	60	38
B381779		52	70	27
B381780		50	10	31
B381785		66	20	64
B381786		29	80	32

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1
B381787		3.88	0.129				<0.5	6.61	1360	1460	2.7	2	2.25	<0.5	9	26
B381788		5.48	0.513				<0.5	6.84	2160	1640	2.8	6	2.12	<0.5	15	52
B381794		5.70	0.134				<0.5	8.15	79	1550	3.1	<2	2.05	<0.5	8	29
B381795		6.22	0.225				<0.5	7.02	160	1700	3.0	<2	1.64	<0.5	9	54
B381796		1.36	<0.005				<0.5	0.12	<5	20	<0.5	<2	20.4	<0.5	2	2
B381797		6.44	0.090				<0.5	7.79	409	1630	3.0	<2	1.86	<0.5	10	56
B381814		1.98	>10.0			14.00	10.1	1.82	2560	150	0.7	385	2.99	1.7	18	13
B381815		4.90	0.977				1.5	7.70	2790	670	3.1	43	2.76	1.7	22	56
B381816		1.66	0.008				<0.5	0.23	37	20	<0.5	<2	20.6	<0.5	1	4
B381817		5.12	0.008				<0.5	0.52	7	10	<0.5	<2	1.30	<0.5	1	5
B381818		3.90	1.805				1.5	5.23	8810	250	1.4	45	0.50	<0.5	82	50
B381824		6.02	0.066				<0.5	7.75	189	1730	3.0	<2	1.92	<0.5	9	50
B381825		5.24	0.062				<0.5	7.55	544	1500	3.0	<2	1.90	<0.5	11	47
B381826		5.38	0.432				1.5	6.58	637	1360	2.5	9	2.25	1.6	9	51
B381827		5.74	0.077				0.6	7.14	927	1510	3.0	<2	2.34	0.7	9	46
B381828		5.94	0.045				<0.5	7.41	290	1550	2.8	<2	2.07	<0.5	9	46
B381829		0.04	0.046													
B381830		0.10	0.094				0.5	7.05	112	590	2.7	<2	0.52	<0.5	59	1230
B381831		6.06	0.243				1.2	6.75	531	1380	2.4	8	2.14	<0.5	11	43
B381835		1.98	0.325				0.7	7.44	251	1130	3.3	<2	1.80	<0.5	12	43
B381836		1.60	<0.005				<0.5	0.15	<5	20	<0.5	<2	20.4	<0.5	1	4
B381837		3.98	2.19				<0.5	7.21	176	1650	2.8	61	1.58	<0.5	12	46
B381838		6.52	0.918				<0.5	7.43	261	1760	2.8	22	1.92	<0.5	9	46
B381842		3.16	0.847				<0.5	6.98	182	1670	3.0	9	2.03	<0.5	11	45
B381843		4.84	0.276				<0.5	6.72	605	1510	2.7	3	1.87	<0.5	10	42
B381844		5.30	0.107				<0.5	7.39	715	1590	3.2	<2	1.89	<0.5	10	41
B381867		6.36	1.035				0.9	7.06	5400	1500	2.5	26	2.05	<0.5	18	54
B381868		6.84	0.743				0.9	7.57	353	1680	3.1	7	2.51	<0.5	13	49
B381869		0.04	0.665													
B381870		0.10	3.01				2.7	6.79	6	2090	3.3	<2	4.69	<0.5	26	140
B381871		6.34	2.15				0.9	6.77	83	1210	2.6	9	2.56	<0.5	10	51

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method	ME-ICP61	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Cu	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti
	Units	ppm	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%
	LOR	1	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01
B381787		38	2.23	0.01	3.42	0.78	239	1	1.37	18	580	23	0.23	9	423	0.29
B381788		41	2.34	0.01	3.76	0.80	239	1	1.34	21	620	24	0.27	6	440	0.29
B381794		20	2.15	0.01	3.91	0.75	219	1	1.54	26	670	31	0.11	14	412	0.29
B381795		25	2.28	0.01	3.49	0.76	217	1	1.35	18	650	28	0.27	10	378	0.29
B381796		2	0.10	<0.01	0.04	11.55	145	<1	0.01	1	480	5	<0.01	<5	106	<0.01
B381797		35	2.42	0.01	3.87	0.79	231	2	1.37	22	650	25	0.20	10	380	0.30
B381814		60	2.19	0.01	0.80	0.13	462	10	0.03	9	150	2220	2.24	815	87	0.05
B381815		63	2.21	0.03	3.57	0.48	567	2	0.06	22	660	267	1.60	68	70	0.28
B381816		3	0.15	<0.01	0.08	11.85	157	<1	0.01	8	540	9	0.05	<5	114	<0.01
B381817		4	0.37	<0.01	0.14	0.72	33	<1	0.01	3	60	4	<0.01	<5	13	0.03
B381818		52	3.97	0.01	3.42	0.52	107	6	0.17	25	410	96	3.00	54	133	0.13
B381824		24	2.66	0.01	4.14	0.59	384	<1	0.87	22	690	33	0.20	26	277	0.30
B381825		40	2.66	0.01	4.01	0.65	506	1	0.68	24	680	59	0.38	23	211	0.30
B381826		44	2.51	0.03	3.65	0.57	557	3	0.65	19	570	169	0.91	31	229	0.25
B381827		30	2.02	0.02	4.02	0.45	547	1	0.81	23	630	81	0.41	20	210	0.30
B381828		24	2.32	0.01	4.20	0.48	445	2	0.83	19	640	53	0.41	26	210	0.27
B381829																
B381830		402	8.27	0.03	2.16	0.58	386	9	0.12	485	360	155	0.01	11	50	0.23
B381831		41	2.14	0.02	3.74	0.63	497	4	0.67	18	540	112	0.34	19	224	0.24
B381835		53	3.21	0.03	3.40	0.64	424	6	0.47	23	650	68	1.74	24	200	0.27
B381836		2	0.12	<0.01	0.04	11.70	169	<1	0.01	7	550	5	<0.01	<5	114	<0.01
B381837		67	2.79	0.01	3.63	0.79	268	3	1.08	19	620	48	0.52	17	327	0.29
B381838		44	2.52	0.04	3.67	1.01	299	2	1.20	20	650	24	0.15	<5	456	0.31
B381842		48	2.35	0.01	3.78	0.82	262	<1	1.57	19	660	23	0.20	<5	475	0.32
B381843		45	2.20	0.01	3.66	0.79	251	3	1.33	19	600	24	0.15	<5	437	0.28
B381844		26	2.28	0.01	3.63	0.86	289	9	1.39	21	640	29	0.12	<5	473	0.30
B381867		88	2.91	0.01	4.14	1.00	216	5	1.11	19	620	34	0.72	18	434	0.28
B381868		103	2.66	0.02	4.21	1.12	240	3	1.19	17	690	18	0.48	<5	543	0.31
B381869																
B381870		105	4.86	<0.01	3.34	2.84	1030	13	2.22	68	2310	35	0.32	<5	1600	0.32
B381871		43	2.66	0.01	3.89	1.30	380	2	1.15	15	670	67	0.32	15	486	0.30

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 28-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058632

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	V	W	Zn
	Units	ppm	ppm	ppm
	LOR	1	10	2
B381787		35	30	46
B381788		36	30	48
B381794		35	20	58
B381795		38	10	58
B381796		1	<10	7
B381797		37	30	56
B381814		7	10	251
B381815		37	50	287
B381816		2	<10	11
B381817		3	<10	2
B381818		24	30	54
B381824		38	10	72
B381825		39	20	124
B381826		33	20	289
B381827		38	20	148
B381828		37	10	92
B381829				
B381830		93	30	636
B381831		31	40	108
B381835		35	30	130
B381836		1	<10	8
B381837		36	20	51
B381838		37	20	55
B381842		39	80	53
B381843		34	40	51
B381844		36	40	65
B381867		44	30	39
B381868		45	30	25
B381869				
B381870		164	<10	100
B381871		46	10	63

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da 7-JUL-2005
Account: STRGOL

CERTIFICATE VA05058634

Project: Dublin Gulch-1735

P.O. No.:

This report is for 32 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 27-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058634

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B 381888		5.58	0.122	<0.5	7.76	164	1270	2.7	7	2.40	<0.5	10	71	22	3.18	<0.01
B 381889		0.04	0.069													
B 381890		0.10	0.452	2.6	8.72	<5	1020	1.2	<2	1.52	<0.5	7	8	7080	3.16	0.03
B 381891		5.20	0.074	<0.5	8.11	398	1440	2.5	7	2.44	<0.5	11	77	30	3.52	<0.01
B 381892		6.44	0.043	<0.5	7.68	273	1330	2.4	3	2.47	<0.5	12	64	22	3.25	<0.01
B 381897		5.36	0.090	<0.5	7.76	348	1320	2.4	6	2.53	<0.5	13	78	17	3.45	0.01
B 381898		6.20	0.049	<0.5	7.89	486	1340	2.4	5	2.95	<0.5	13	72	11	3.35	0.01
B 381899		6.50	0.062	<0.5	7.73	348	1370	2.4	3	2.63	<0.5	12	82	14	3.44	0.01
B 381914		5.18	0.077	<0.5	7.85	240	1410	2.3	9	2.55	<0.5	11	95	11	3.46	0.01
B 381915		1.66	0.190	<0.5	7.51	344	1320	2.1	25	2.48	<0.5	11	62	9	3.10	0.01
B 381916		1.32	<0.005	<0.5	0.15	<5	20	<0.5	<2	19.35	<0.5	<1	2	3	0.13	<0.01
B 381917		2.50	0.328	<0.5	7.76	277	1260	2.3	38	2.39	<0.5	9	59	9	3.17	<0.01
B 381918		1.68	0.015	<0.5	7.85	150	1370	2.3	<2	2.57	<0.5	12	87	12	3.45	0.01
B 382116		2.22	<0.005	<0.5	0.10	<5	10	<0.5	<2	18.10	<0.5	<1	<1	2	0.10	<0.01
B 382117		2.34	0.125	<0.5	7.31	4170	1600	2.6	10	2.03	<0.5	8	17	45	2.41	0.01
B 382118		3.14	0.044	<0.5	7.43	1585	1630	3.1	4	2.06	<0.5	5	34	29	2.42	0.01
B 382119		5.90	4.85	19.0	5.28	4650	70	2.1	262	2.80	16.0	5	19	2940	7.17	0.69
B 382120		2.08	0.290	<0.5	6.53	4110	1240	2.4	11	2.03	<0.5	5	49	27	2.22	0.01
B 382121		1.22	0.024	<0.5	7.22	697	1140	3.4	4	1.58	<0.5	4	21	20	1.91	0.01
B 382122		1.26	0.019	<0.5	7.61	860	1300	3.6	3	1.69	<0.5	5	58	24	1.99	0.01
B 382123		1.52	0.024	<0.5	7.25	848	1340	3.4	4	1.21	<0.5	4	21	19	2.10	0.01
B 382124		5.02	0.035	<0.5	7.12	2150	1340	3.2	12	2.17	<0.5	5	55	20	2.12	0.02
B 382140		5.96	0.358	<0.5	2.64	7790	540	2.1	32	1.19	0.5	9	24	39	1.00	0.01
B 382141		2.04	0.086	<0.5	7.24	5810	1420	3.0	20	2.07	<0.5	8	33	37	2.75	0.01
B 382142		1.92	0.079	<0.5	7.40	3460	1460	3.1	9	2.32	<0.5	7	40	32	2.57	0.01
B 382143		2.46	0.054	<0.5	7.28	1235	1420	2.8	10	2.33	<0.5	6	26	45	2.10	0.01
B 382144		4.64	0.501	<0.5	5.26	>10000	950	2.0	93	2.29	<0.5	5	48	30	3.37	0.01
B 382152		4.02	0.024	<0.5	7.28	571	1520	3.2	<2	2.39	<0.5	7	31	30	2.42	<0.01
B 382153		2.40	0.202	<0.5	6.89	>10000	1400	2.4	9	1.32	<0.5	8	43	46	2.72	0.06
B 382154		3.26	0.024	<0.5	7.18	608	1540	3.2	2	2.27	<0.5	7	34	26	2.27	0.01
B 382155		1.36	0.094	<0.5	6.96	5270	1480	3.0	11	2.27	<0.5	7	60	22	2.44	0.01
B 382156		1.94	<0.005	<0.5	0.10	12	10	<0.5	<2	18.90	<0.5	<1	3	2	0.09	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 27-JUL-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058634

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B 381888		3.32	1.26	344	1	1.64	34	710	30	0.03	<5	394	0.38	87	10	71
B 381889																
B 381890		3.57	1.14	477	2	3.34	9	1840	13	0.23	<5	652	0.33	163	<10	57
B 381891		3.04	1.44	402	<1	1.64	33	780	30	0.02	<5	413	0.43	106	<10	85
B 381892		2.99	1.36	440	<1	1.62	33	740	29	0.04	<5	422	0.41	98	<10	94
B 381897		2.97	1.43	416	1	1.80	39	760	24	0.02	<5	424	0.44	106	10	83
B 381898		3.09	1.40	423	1	1.66	37	780	22	0.02	<5	436	0.44	106	<10	87
B 381899		2.99	1.39	395	1	1.64	38	800	22	0.04	<5	435	0.44	110	10	84
B 381914		3.08	1.38	412	<1	1.54	39	790	16	0.01	<5	439	0.43	104	<10	89
B 381915		3.06	1.29	365	<1	1.42	36	770	15	0.01	<5	414	0.40	93	10	75
B 381916		0.04	10.90	141	<1	0.02	5	440	2	0.01	<5	123	0.01	2	<10	8
B 381917		3.04	1.28	375	<1	1.49	34	710	19	0.02	<5	413	0.38	90	<10	75
B 381918		2.91	1.39	434	<1	1.59	37	790	22	<0.01	<5	431	0.42	101	20	93
B 382116		0.03	10.35	131	<1	0.01	4	470	<2	0.02	<5	107	<0.01	1	<10	6
B 382117		4.41	0.72	171	1	0.77	16	600	33	0.59	14	370	0.27	32	30	43
B 382118		3.82	0.81	189	1	1.06	19	630	19	0.30	12	450	0.29	34	20	22
B 382119		2.79	0.49	340	1	0.36	10	400	9600	7.22	4860	225	0.18	22	10	2480
B 382120		4.62	0.63	233	5	0.95	11	450	46	0.46	34	308	0.21	25	40	28
B 382121		4.10	0.56	209	2	1.40	11	420	39	0.14	9	356	0.22	24	60	43
B 382122		4.41	0.60	200	1	1.51	13	470	39	0.18	8	391	0.25	28	20	42
B 382123		3.85	0.70	221	1	1.07	14	500	41	0.11	7	368	0.25	27	20	52
B 382124		4.02	0.70	217	4	1.24	15	510	41	0.21	10	402	0.26	29	20	43
B 382140		3.67	0.34	89	2	0.58	15	270	8	0.34	5	134	0.24	27	20	18
B 382141		3.51	0.75	178	1	1.43	19	570	34	0.53	12	439	0.30	36	10	33
B 382142		3.50	0.75	193	1	1.51	19	590	26	0.37	6	463	0.30	34	10	33
B 382143		3.73	0.70	164	1	1.15	20	590	27	0.28	<5	430	0.30	34	20	29
B 382144		2.65	0.52	147	1	0.81	13	420	17	1.15	17	315	0.21	24	20	19
B 382152		3.70	0.77	219	4	1.64	22	610	18	0.27	<5	471	0.31	36	10	30
B 382153		3.64	0.77	140	3	0.86	17	530	19	0.91	21	369	0.27	31	20	24
B 382154		4.01	0.72	208	1	1.62	25	590	20	0.25	<5	457	0.32	47	10	29
B 382155		3.73	0.72	182	2	1.61	20	580	17	0.49	8	476	0.30	34	10	24
B 382156		0.03	11.05	149	<1	0.01	3	430	3	0.01	<5	101	<0.01	2	<10	7

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05058633

Project: Dublin Gulch-1735

P.O. No.:

This report is for 54 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Pb-AA62	Ore grade Pb - four acid / AAS	AAS
Zn-AA62	Ore grade Zn - four acid / AAS	AAS

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B381949		0.04	0.250	1.3	8.01	4690	1230	3.4	14	2.06	0.5	12	150	84	3.03	0.05
B381950		0.10	1.475	<0.5	7.31	1320	730	6.3	<2	0.01	<0.5	5	227	40	4.00	0.07
B381951		2.92	0.025	<0.5	7.66	854	1350	3.6	<2	1.88	<0.5	8	29	67	2.03	0.02
B381952		5.56	0.024	<0.5	7.11	460	1350	3.6	<2	1.90	<0.5	8	61	64	2.09	0.02
B381953		4.38	0.038	<0.5	7.87	2430	1400	3.6	3	1.80	<0.5	7	30	73	2.11	0.01
B381954		4.86	0.032	<0.5	7.73	1195	1400	3.8	<2	1.94	<0.5	7	59	84	2.26	0.02
B381955		0.50	0.039	4.9	7.18	785	1300	2.9	<2	1.76	<0.5	6	38	67	2.40	0.02
B381956		1.76	<0.005	<0.5	0.12	9	20	<0.5	<2	20.9	<0.5	2	4	3	0.12	<0.01
B381957		4.02	0.034	1.2	8.06	871	1420	3.8	3	2.10	<0.5	8	33	76	2.38	0.01
B381958		0.76	0.029	1.8	4.24	944	610	1.4	2	1.37	<0.5	6	81	33	1.85	0.01
B381959		4.40	0.160	1.2	7.20	1315	1330	3.3	10	2.08	<0.5	11	35	76	2.92	0.01
B381960		1.22	0.193	9.0	6.12	713	3570	2.4	4	1.66	<0.5	6	93	74	2.54	0.01
B381972		1.16	0.364	14.6	5.87	402	250	2.3	5	1.96	83.9	4	24	171	8.82	0.51
B381973		5.16	0.018	4.1	7.79	705	1010	3.0	<2	2.20	7.9	9	72	98	2.94	0.06
B381974		5.18	0.014	0.5	6.82	680	1280	2.6	<2	2.01	4.0	8	38	103	2.85	0.06
B381975		1.82	0.082	2.2	7.17	3420	900	2.9	5	1.92	5.3	14	58	103	4.05	0.05
B381976		2.24	<0.005	<0.5	0.15	5	20	<0.5	<2	19.20	<0.5	<1	2	10	0.13	<0.01
B381988		5.06	0.097	<0.5	7.53	3010	1400	3.6	12	1.94	<0.5	7	60	105	2.22	0.01
B381989		0.04	0.104													
B381990		0.10	3.23	0.5	6.67	5	2070	3.1	<2	4.67	<0.5	22	132	94	4.89	0.02
B381991		3.88	0.132	0.5	7.53	8190	1270	3.3	33	2.05	<0.5	8	34	94	3.04	0.02
B381992		1.02	0.235	0.6	7.85	4330	1440	3.5	15	1.68	<0.5	5	35	118	2.37	0.01
B381993		5.40	0.048	<0.5	7.84	2960	1440	3.7	6	2.16	<0.5	7	68	94	2.54	0.01
B382013		3.56	0.025	<0.5	7.81	1050	1430	3.2	<2	2.13	<0.5	5	33	59	2.04	0.02
B382014		3.88	0.048	<0.5	7.02	3500	1210	2.4	6	2.93	<0.5	5	44	63	2.45	0.02
B382015		2.98	0.103	<0.5	6.53	9560	1130	2.3	11	3.91	<0.5	9	44	53	3.05	0.04
B382016		2.08	<0.005	<0.5	0.11	9	10	<0.5	<2	20.1	<0.5	<1	2	3	0.12	<0.01
B382017		2.50	0.037	<0.5	7.94	2850	1440	3.0	9	1.74	<0.5	6	58	96	2.24	0.01
B382022		2.04	0.468	<0.5	7.78	>10000	1590	2.5	132	2.50	<0.5	10	53	138	2.81	0.03
B382023		4.58	0.050	<0.5	7.86	2800	1510	3.2	12	1.81	<0.5	6	29	42	2.32	0.01
B382024		5.50	0.103	0.5	7.71	5420	1500	3.0	14	2.28	<0.5	8	64	68	2.53	0.01
B382025		4.32	0.072	<0.5	7.49	3730	1600	3.0	19	1.62	<0.5	7	30	61	2.17	0.09
B382046		6.68	0.051	<0.5	7.83	3110	1590	3.5	11	2.01	<0.5	6	54	75	2.10	0.04
B382047		7.08	0.105	<0.5	7.79	2610	1620	3.4	38	2.51	<0.5	7	30	54	2.37	0.02
B382048		6.86	0.430	<0.5	7.50	5070	1520	3.5	14	2.25	<0.5	6	59	78	2.39	0.12
B382049		0.04	0.076													
B382050		0.10	0.887	2.4	7.63	15	450	0.7	<2	1.88	<0.5	21	101	2030	5.03	0.02
B382063		5.84	0.053	<0.5	7.81	3220	1470	4.6	12	1.64	<0.5	5	45	158	1.93	0.02
B382064		6.34	0.079	<0.5	7.83	4450	1610	4.5	31	1.82	<0.5	5	30	118	2.07	0.01
B382065		7.26	0.095	<0.5	7.13	5510	1560	4.3	14	1.91	<0.5	5	47	114	2.02	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B381949		4.11	0.80	298	2	0.92	13	610	253	0.77	41	314	0.27	42	30	209
B381950		2.85	0.37	92	2	0.12	17	330	34	0.02	125	98	0.28	96	10	48
B381951		4.07	0.68	178	1	1.36	6	620	28	0.31	9	370	0.27	41	20	31
B381952		3.89	0.78	187	1	1.16	8	590	17	0.42	9	341	0.26	42	20	23
B381953		4.43	0.78	158	2	1.26	7	590	14	0.43	9	358	0.27	41	30	18
B381954		4.30	0.81	210	1	1.18	10	610	40	0.59	16	362	0.27	41	30	49
B381955		3.79	0.70	259	8	1.36	12	440	30	0.20	6	401	0.23	37	60	43
B381956		0.03	12.45	165	<1	0.01	2	570	<2	0.02	<5	118	<0.01	1	<10	8
B381957		4.49	0.92	256	2	1.16	7	610	27	0.49	9	346	0.27	43	30	34
B381958		1.65	0.61	336	5	0.84	15	360	12	0.15	5	194	0.18	33	30	36
B381959		3.95	0.87	313	1	0.66	9	570	50	0.89	19	275	0.26	41	20	66
B381960		3.32	0.64	286	11	1.03	16	380	25	0.18	9	365	0.20	32	100	46
B381972		2.66	0.80	3390	<1	0.02	14	440	>10000	7.58	7140	48	0.15	31	10	>10000
B381973		3.94	0.83	1345	<1	0.08	13	630	930	0.73	155	115	0.25	43	20	1205
B381974		4.27	0.69	666	<1	0.10	11	610	204	0.65	47	168	0.26	41	30	638
B381975		3.82	0.88	861	2	0.07	10	570	431	1.75	43	123	0.22	36	30	831
B381976		0.04	10.85	147	<1	0.01	5	460	4	0.02	<5	115	0.01	1	<10	9
B381988		4.40	0.71	134	1	1.57	9	560	11	0.58	<5	517	0.27	45	20	15
B381989																
B381990		3.14	2.77	993	13	2.16	61	2220	29	0.31	<5	1585	0.35	159	10	90
B381991		3.95	0.90	160	2	1.06	11	600	20	1.18	12	375	0.25	41	20	35
B381992		4.68	0.79	128	4	1.25	11	600	11	0.66	<5	481	0.26	42	20	15
B381993		4.13	0.89	156	2	1.52	11	600	10	0.54	<5	584	0.27	43	40	16
B382013		4.22	0.70	146	1	1.72	14	610	14	0.48	<5	526	0.28	40	<10	19
B382014		3.87	1.41	198	<1	1.32	13	540	9	0.56	5	489	0.24	35	20	14
B382015		3.12	1.69	233	1	1.24	14	490	6	1.00	7	536	0.23	32	10	11
B382016		0.03	11.40	172	<1	0.01	3	460	8	0.01	<5	113	<0.01	1	<10	11
B382017		4.36	0.83	117	1	1.54	16	620	10	0.50	<5	524	0.28	41	20	17
B382022		5.41	0.95	178	8	1.14	14	580	12	0.84	21	499	0.27	34	50	17
B382023		4.08	0.76	153	3	1.49	19	600	15	0.42	<5	495	0.29	36	30	20
B382024		4.18	1.05	152	1	1.12	18	610	13	0.62	5	493	0.27	36	30	15
B382025		4.07	0.78	127	1	1.39	16	600	13	0.44	5	555	0.27	36	30	16
B382046		4.43	0.71	120	2	1.58	12	590	10	0.43	5	585	0.27	33	20	16
B382047		4.18	0.82	144	3	1.41	15	610	16	0.49	<5	570	0.29	35	20	16
B382048		4.15	0.68	122	1	1.49	17	610	11	0.63	<5	532	0.28	35	10	15
B382049																
B382050		1.71	1.31	419	3	3.13	48	650	14	0.61	<5	216	0.30	91	<10	195
B382063		4.20	0.65	60	<1	1.46	10	540	11	0.66	<5	437	0.20	43	<10	14
B382064		4.07	0.88	72	1	1.27	11	580	9	0.63	5	488	0.22	45	10	13
B382065		4.06	0.83	66	1	1.28	13	570	5	0.56	<5	473	0.21	45	10	12

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method	Pb-AA62	Zn-AA62
	Analyte	Pb	Zn
	Units	%	%
	LOR	0.01	0.01
B381949			
B381950			
B381951			
B381952			
B381953			
B381954			
B381955			
B381956			
B381957			
B381958			
B381959			
B381960			
B381972		1.63	1.25
B381973			
B381974			
B381975			
B381976			
B381988			
B381989			
B381990			
B381991			
B381992			
B381993			
B382013			
B382014			
B382015			
B382016			
B382017			
B382022			
B382023			
B382024			
B382025			
B382046			
B382047			
B382048			
B382049			
B382050			
B382063			
B382064			
B382065			

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B382066		5.94	0.039	<0.5	7.59	4360	1640	4.8	8	1.98	<0.5	5	35	132	2.15	0.01
B382067		6.18	0.041	<0.5	7.75	3950	1540	4.7	6	1.82	<0.5	5	53	144	2.11	0.01
B382068		5.70	0.136	<0.5	7.41	5750	1380	4.8	45	1.66	<0.5	5	30	113	1.83	0.01
B382069		0.04	0.191													
B382070		0.10	1.440	<0.5	6.90	1225	710	5.9	<2	0.01	<0.5	5	213	36	3.80	0.05
B382071		3.40	0.099	<0.5	7.03	3750	1210	5.1	27	1.73	<0.5	5	43	104	1.53	0.01
B382072		2.36	0.282	<0.5	7.09	4570	1640	3.6	70	1.88	<0.5	10	27	58	2.30	0.01
B382073		2.42	0.205	<0.5	7.06	3450	850	3.3	21	2.14	<0.5	5	43	79	2.29	0.02
B382074		4.42	0.097	<0.5	6.88	5170	1330	3.9	8	3.47	<0.5	5	23	80	1.92	<0.01
B382075		3.92	0.053	<0.5	7.37	2540	1500	3.0	3	2.36	<0.5	6	50	42	2.22	<0.01
B382085		4.04	0.047	<0.5	7.36	1860	1470	3.2	7	2.13	<0.5	5	27	59	2.33	<0.01
B382086		3.08	0.131	<0.5	7.49	1490	1530	3.3	18	2.06	<0.5	4	49	40	2.31	0.01
B382087		2.22	0.025	<0.5	7.90	728	1590	3.1	<2	1.88	<0.5	5	25	29	2.36	0.01
B382088		2.44	0.502	<0.5	7.74	>10000	1780	2.2	39	2.53	<0.5	11	47	38	3.18	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B382066		4.01	0.83	68	1	1.55	12	590	9	0.59	<5	516	0.22	46	10	12
B382067		3.93	0.79	67	1	1.54	12	550	11	0.60	5	486	0.21	44	<10	12
B382068		4.06	0.66	64	<1	1.61	9	500	12	0.50	<5	447	0.18	39	10	14
B382069																
B382070		2.62	0.35	88	2	0.11	20	320	23	0.02	114	92	0.22	89	20	45
B382071		3.76	0.48	63	1	1.63	9	430	12	0.51	7	377	0.15	34	10	17
B382072		3.75	0.65	131	2	1.39	17	570	23	0.52	12	403	0.24	36	30	20
B382073		3.37	0.81	205	<1	0.79	13	500	12	0.69	11	191	0.19	34	20	29
B382074		3.87	0.65	126	1	1.42	11	440	8	0.55	<5	429	0.18	32	10	21
B382075		3.74	0.70	166	1	1.13	21	590	15	0.39	<5	426	0.28	34	10	26
B382085		3.90	0.62	174	<1	1.37	18	560	29	0.52	6	425	0.26	31	10	36
B382086		3.88	0.68	186	3	1.45	18	570	28	0.31	6	460	0.27	33	20	36
B382087		3.52	0.79	207	1	1.29	19	640	21	0.23	<5	496	0.28	33	10	43
B382088		5.15	0.80	178	1	0.80	17	620	26	0.99	21	501	0.27	33	50	21

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05058633

Sample Description	Method / Analyte / Units / LOR	Pb-AA62 Pb % 0.01	Zn-AA62 Zn % 0.01
B382066			
B382067			
B382068			
B382069			
B382070			
B382071			
B382072			
B382073			
B382074			
B382075			
B382085			
B382086			
B382087			
B382088			

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 2-AUG-2005
Account: STRGOL

CERTIFICATE VA05060563

Project: Dublin Gulch-1735

P.O. No.:

This report is for 113 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 21-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380443		2.50	0.057	<0.5	6.75	3200	990	3.4	6	2.09	<0.5	7	34	67	2.54	0.01
B380444		6.50	0.377	0.5	6.88	3670	790	3.4	7	2.37	<0.5	9	32	146	3.46	0.02
B380445		4.44	0.029	<0.5	7.56	1050	1360	3.0	2	1.95	<0.5	8	32	24	2.46	0.01
B380446		4.28	0.028	<0.5	7.40	477	1280	3.0	3	1.70	<0.5	8	35	41	2.41	0.01
B380447		6.24	0.078	<0.5	7.22	2410	1410	3.5	11	2.76	<0.5	10	38	87	2.77	0.01
B380448		5.98	0.317	<0.5	7.18	4350	1440	3.1	72	1.98	<0.5	12	37	106	2.69	0.01
B380449		0.04	0.322													
B380450		0.12	0.100	0.5	6.85	118	570	2.5	<2	0.51	<0.5	58	1145	383	8.31	0.04
B380451		4.12	0.230	0.5	7.28	7350	1460	2.4	37	1.22	<0.5	13	37	87	2.76	0.01
B380452		3.62	0.354	1.1	7.31	>10000	1480	2.3	34	1.34	<0.5	29	35	95	4.19	0.03
B380453		4.06	0.128	<0.5	7.40	5490	1440	2.6	11	1.37	<0.5	9	35	112	2.49	0.01
B380454		0.80	1.815	1.5	3.66	>10000	170	1.4	278	1.60	<0.5	253	21	39	13.00	0.02
B380455		0.90	0.059	<0.5	7.35	2130	1420	3.0	6	1.54	<0.5	8	44	148	2.43	0.01
B380456		1.64	<0.005	<0.5	0.13	79	20	<0.5	<2	18.25	<0.5	2	2	2	0.14	<0.01
B380457		5.42	0.069	<0.5	7.03	2590	1270	2.7	7	1.81	<0.5	9	34	67	2.47	0.01
B380458		5.48	0.076	<0.5	7.56	2770	1260	2.9	11	2.13	<0.5	9	36	58	2.64	0.01
B380459		4.54	0.047	<0.5	7.47	2020	1260	2.8	7	2.21	<0.5	8	37	43	2.57	0.01
B380460		5.72	0.083	<0.5	7.35	2560	1270	2.9	7	1.83	<0.5	10	39	78	2.57	0.01
B380461		2.84	0.098	<0.5	7.27	1870	1410	3.2	8	2.43	<0.5	9	41	95	2.84	0.01
B380462		3.24	0.080	<0.5	7.44	1685	1420	3.1	7	2.43	<0.5	8	40	84	2.73	<0.01
B380463		5.16	0.136	<0.5	6.74	2710	1150	3.7	12	2.39	<0.5	6	33	66	2.31	<0.01
B380464		4.90	0.073	<0.5	6.66	1995	1020	3.5	12	2.19	<0.5	4	31	138	2.20	0.01
B380465		4.28	0.072	<0.5	6.96	1540	1020	3.5	6	2.29	<0.5	7	34	156	2.36	0.01
B380466		2.40	0.127	<0.5	6.97	6910	1300	4.2	15	1.34	<0.5	5	26	71	1.76	0.01
B380473		3.08	0.053	<0.5	6.93	5480	1300	4.4	10	1.28	<0.5	5	22	75	1.62	0.03
B380474		3.02	0.124	<0.5	6.99	6150	1200	4.8	9	1.43	<0.5	4	23	85	1.70	0.02
B380475		4.38	0.132	<0.5	7.09	4460	1210	4.7	46	0.97	<0.5	2	24	92	1.68	0.03
B380476		1.76	<0.005	<0.5	0.10	7	10	<0.5	<2	18.75	<0.5	<1	1	2	0.11	<0.01
B380477		6.10	0.171	<0.5	7.05	7680	1320	3.3	21	1.97	<0.5	10	31	72	2.61	0.01
B380487		4.26	0.148	<0.5	6.81	4130	1280	3.2	16	2.45	<0.5	4	34	62	2.36	0.01
B380488		5.66	0.178	<0.5	6.48	5610	1260	3.2	26	2.48	<0.5	7	33	70	2.38	0.01
B380489		0.02	0.172													
B380490		0.12	4.55	9.3	7.08	16	460	0.9	<2	2.85	0.9	16	20	123	3.97	0.04
B380491		5.20	0.108	<0.5	6.97	4980	1340	2.9	19	1.56	<0.5	7	29	70	2.28	0.01
B380501		3.20	0.280	<0.5	6.77	6320	1390	3.0	23	1.98	<0.5	6	24	70	2.19	0.01
B380502		3.42	0.278	<0.5	6.91	6260	1400	3.0	17	2.33	<0.5	6	25	69	2.27	0.01
B380503		6.24	0.377	<0.5	6.78	5010	1370	3.1	28	2.03	<0.5	6	25	72	2.21	<0.01
B380504		6.08	0.361	<0.5	7.15	6560	1340	3.3	36	1.47	<0.5	7	27	39	2.34	<0.01
B380505		6.36	0.216	5.1	6.97	4890	1440	2.9	25	1.87	<0.5	7	26	51	2.27	<0.01
B380506		5.88	0.206	1.9	7.17	5980	1400	3.2	21	2.07	<0.5	7	29	59	2.36	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380443		3.84	0.81	232	<1	0.68	9	590	17	0.29	11	234	0.27	41	20	28
B380444		3.26	0.90	268	<1	0.52	12	610	32	1.56	11	197	0.26	39	20	56
B380445		3.70	0.85	231	<1	1.34	12	630	22	0.19	5	418	0.28	39	20	34
B380446		3.57	0.82	197	<1	1.19	10	610	19	0.26	<5	372	0.28	42	10	29
B380447		3.73	0.95	205	<1	1.49	12	650	16	0.63	<5	497	0.30	47	20	18
B380448		4.20	0.80	172	1	1.16	11	630	25	0.55	7	383	0.28	45	20	21
B380449																
B380450		2.12	0.58	375	8	0.12	459	340	145	0.02	16	49	0.25	87	30	604
B380451		5.05	0.82	196	1	0.70	10	600	27	0.58	10	240	0.24	44	30	61
B380452		5.40	0.94	191	<1	0.63	15	620	43	1.42	20	243	0.24	43	30	36
B380453		4.75	0.84	143	<1	0.82	10	690	16	0.46	9	284	0.28	45	30	22
B380454		2.23	0.86	154	2	0.18	35	300	172	6.73	68	104	0.10	21	20	14
B380455		3.66	0.83	123	<1	1.28	11	740	13	0.23	9	406	0.32	50	20	18
B380456		0.03	11.25	150	<1	0.01	3	530	<2	0.02	<5	111	0.01	2	<10	7
B380457		3.78	0.81	171	<1	1.40	11	610	17	0.27	<5	399	0.28	41	10	22
B380458		3.96	0.87	211	<1	1.70	11	630	22	0.24	5	503	0.29	44	50	30
B380459		3.68	0.90	236	1	1.76	11	620	23	0.18	<5	535	0.28	45	10	32
B380460		3.92	0.79	188	<1	1.65	12	650	18	0.23	<5	501	0.31	47	10	24
B380461		3.71	0.83	194	1	1.74	12	720	20	0.45	5	553	0.33	51	20	26
B380462		3.77	0.82	193	1	1.74	11	700	17	0.39	<5	554	0.32	48	20	24
B380463		4.28	0.74	170	2	1.73	9	550	17	0.46	<5	524	0.27	40	10	32
B380464		4.04	0.73	140	2	1.34	11	520	12	0.48	<5	425	0.25	39	20	23
B380465		4.18	0.80	120	<1	1.22	13	560	13	0.63	<5	451	0.26	40	10	24
B380466		5.20	0.61	89	1	1.15	8	390	13	0.58	6	311	0.14	32	10	27
B380473		4.42	0.64	83	2	1.24	5	380	15	0.63	5	311	0.15	32	10	29
B380474		4.53	0.47	84	1	1.33	9	420	22	0.64	<5	321	0.14	32	10	40
B380475		4.41	0.55	83	1	1.38	7	400	50	0.52	8	306	0.15	33	10	42
B380476		0.03	10.65	153	<1	0.01	2	430	3	0.02	<5	109	<0.01	1	<10	5
B380477		4.06	0.76	130	2	1.49	14	570	18	0.70	<5	456	0.27	38	20	29
B380487		4.37	0.83	140	2	1.63	12	590	15	0.43	<5	504	0.28	43	10	26
B380488		4.12	0.80	141	2	1.48	11	550	18	0.48	6	456	0.26	41	10	26
B380489																
B380490		2.21	1.28	925	13	1.67	13	850	30	0.68	<5	417	0.36	146	<10	110
B380491		4.08	0.87	130	1	1.26	13	550	23	0.45	8	388	0.27	37	10	29
B380501		4.22	0.87	106	2	1.48	18	510	19	0.53	5	499	0.28	33	10	22
B380502		4.28	0.93	116	2	1.42	18	580	20	0.54	5	505	0.28	34	10	22
B380503		4.04	0.76	116	2	1.56	15	560	21	0.51	5	488	0.27	34	10	23
B380504		3.99	0.84	128	6	1.39	13	470	20	0.47	5	443	0.24	38	10	30
B380505		3.92	0.80	138	10	1.40	14	520	21	0.41	5	436	0.25	34	10	28
B380506		4.17	0.83	140	1	1.48	15	550	18	0.49	<5	458	0.26	40	10	28

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380507		6.30	0.114	<0.5	6.62	4320	1340	3.0	14	2.43	<0.5	5	27	44	2.20	<0.01
B380508		4.04	0.133	<0.5	6.89	4580	1390	3.0	10	1.98	<0.5	6	29	52	2.26	<0.01
B380509		0.04	0.140													
B380510		0.10	1.470	<0.5	6.84	1260	690	6.1	<2	0.01	<0.5	4	209	39	3.67	0.06
B380511		4.20	0.248	0.6	7.26	3510	1410	3.2	13	2.27	<0.5	6	34	56	2.26	<0.01
B380512		5.94	0.089	<0.5	7.25	4020	1360	3.3	9	2.20	<0.5	6	27	54	2.37	<0.01
B380513		5.14	0.201	<0.5	7.16	4880	1460	3.1	15	1.78	<0.5	6	26	54	2.37	<0.01
B380514		5.50	0.302	<0.5	7.25	7050	1520	3.0	26	1.73	<0.5	7	28	61	2.54	<0.01
B380515		2.24	0.239	<0.5	7.39	7600	1540	2.9	21	1.44	<0.5	8	29	78	2.50	<0.01
B380516		1.68	<0.005	0.7	0.10	28	10	<0.5	<2	19.50	<0.5	<1	2	1	0.11	<0.01
B380517		3.98	0.328	1.3	6.93	7760	890	3.1	28	3.16	<0.5	9	49	64	2.32	<0.01
B380518		5.90	0.330	<0.5	6.69	8000	1140	2.7	27	3.10	<0.5	6	25	51	2.51	0.01
B380519		5.46	0.488	<0.5	7.17	>10000	1340	2.6	22	2.27	<0.5	9	47	67	2.53	<0.01
B380520		6.00	0.316	<0.5	7.27	7960	1540	3.1	17	1.89	<0.5	8	28	56	2.52	<0.01
B380521		2.82	0.562	<0.5	7.30	>10000	1590	2.6	38	1.98	<0.5	9	43	74	2.69	<0.01
B380522		3.04	0.437	<0.5	6.91	>10000	1540	2.6	36	1.80	<0.5	9	28	70	2.59	<0.01
B380523		2.40	0.577	0.6	7.28	>10000	1610	2.7	34	2.19	<0.5	8	46	98	2.93	<0.01
B380524		4.00	0.325	<0.5	7.41	6080	1250	2.9	37	2.69	<0.5	7	25	75	1.98	0.01
B380525		5.68	0.303	<0.5	6.94	5530	1400	2.9	21	2.01	<0.5	8	44	65	2.26	<0.01
B380531		7.04	0.197	<0.5	6.95	4630	1290	3.0	14	1.98	<0.5	6	24	66	1.91	<0.01
B380532		5.86	0.155	<0.5	7.13	3050	1370	3.2	8	2.00	<0.5	6	45	60	2.07	<0.01
B380533		1.90	0.089	<0.5	7.01	2820	1410	3.2	4	1.93	<0.5	7	26	60	1.94	<0.01
B380534		3.30	0.184	3.0	6.26	3180	870	2.2	7	2.94	12.0	7	43	37	2.39	0.14
B380535		5.32	0.244	<0.5	6.68	4280	1520	3.1	15	1.86	<0.5	9	28	69	2.21	<0.01
B380536		1.96	<0.005	<0.5	0.14	<5	20	<0.5	<2	19.25	<0.5	1	5	2	0.12	<0.01
B380537		6.30	0.186	<0.5	6.62	4940	1480	2.8	20	1.96	<0.5	9	29	63	2.50	<0.01
B380538		3.60	0.261	1.6	6.48	7510	920	2.6	27	3.51	<0.5	8	45	40	2.46	0.01
B380539		2.00	0.181	<0.5	6.81	4330	1430	3.1	20	1.74	<0.5	13	30	35	2.38	<0.01
B380544		2.32	0.173	<0.5	6.25	7520	1440	2.2	13	2.56	<0.5	12	43	32	2.03	<0.01
B380545		5.46	0.191	<0.5	7.14	4850	1460	2.8	16	1.88	<0.5	14	25	43	1.92	<0.01
B380546		5.36	0.138	<0.5	7.12	3230	1430	2.8	17	1.90	<0.5	9	41	43	1.90	<0.01
B380547		6.32	0.303	<0.5	6.89	6040	1430	2.8	39	2.02	<0.5	11	26	40	2.11	<0.01
B380548		5.66	0.188	<0.5	6.98	4090	1430	3.0	21	2.43	<0.5	8	44	42	2.22	<0.01
B380549		0.04	0.199													
B380550		0.10	0.098	<0.5	6.60	118	560	2.6	<2	0.53	<0.5	56	1105	380	8.11	0.03
B380551		5.72	0.067	<0.5	7.52	2240	1530	3.3	5	2.31	<0.5	7	26	56	2.11	<0.01
B380552		5.16	0.142	<0.5	6.80	4280	1340	3.1	13	2.16	<0.5	8	33	44	2.26	<0.01
B380560		5.60	0.046	<0.5	6.97	1410	1220	2.9	4	2.60	<0.5	7	40	44	2.35	<0.01
B380561		2.50	0.056	<0.5	6.97	1180	1280	2.8	3	2.52	<0.5	8	37	39	2.20	<0.01
B380562		2.48	0.072	<0.5	7.02	1695	1440	2.9	6	2.36	<0.5	8	40	41	2.42	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380507		3.85	0.82	168	1	1.54	16	460	20	0.38	<5	487	0.25	37	10	30
B380508		3.94	0.78	138	2	1.54	15	520	21	0.41	7	462	0.26	38	<10	28
B380509																
B380510		2.76	0.35	85	2	0.11	20	300	29	0.01	116	96	0.23	91	10	57
B380511		3.96	0.84	150	2	1.66	17	550	19	0.40	<5	522	0.27	43	10	30
B380512		3.73	0.83	144	1	1.75	17	570	19	0.46	5	534	0.29	37	10	31
B380513		4.19	0.96	136	1	1.40	19	560	23	0.43	<5	486	0.29	36	10	29
B380514		4.25	0.96	130	2	1.50	17	600	19	0.53	6	473	0.29	37	10	27
B380515		4.59	0.95	117	2	1.34	19	590	19	0.56	8	433	0.29	39	10	26
B380516		0.03	11.00	133	1	0.01	3	420	5	0.02	<5	111	<0.01	1	10	5
B380517		3.91	0.52	213	3	0.40	18	560	31	0.70	18	238	0.27	35	20	47
B380518		4.25	0.63	162	2	0.77	16	550	30	0.59	13	311	0.25	34	20	31
B380519		4.73	0.57	136	1	0.87	20	570	32	0.79	14	301	0.27	35	20	36
B380520		4.68	0.82	121	3	1.45	20	600	20	0.55	8	456	0.29	37	10	29
B380521		5.04	0.89	121	2	1.14	18	560	17	0.68	12	426	0.27	35	10	27
B380522		4.80	0.84	126	2	1.15	16	590	22	0.65	8	411	0.27	35	10	28
B380523		4.86	0.91	126	4	1.21	19	610	22	0.81	13	437	0.28	37	10	25
B380524		4.53	0.47	158	1	1.05	16	600	29	0.55	21	289	0.30	36	10	40
B380525		4.01	0.75	122	2	1.39	18	560	24	0.47	5	426	0.28	34	10	29
B380531		4.20	0.67	114	<1	1.46	15	530	20	0.38	<5	463	0.27	31	<10	24
B380532		4.08	0.72	127	1	1.63	17	540	21	0.36	<5	483	0.28	34	10	26
B380533		4.32	0.65	140	2	1.37	17	530	25	0.37	14	416	0.28	32	10	25
B380534		3.77	0.39	933	1	0.18	14	640	1335	1.29	77	139	0.23	36	40	1700
B380535		4.29	0.71	144	<1	1.36	18	580	28	0.43	8	420	0.29	34	10	26
B380536		0.04	11.10	159	<1	0.02	1	500	<2	0.02	<5	110	<0.01	1	<10	12
B380537		4.33	0.77	182	1	1.06	20	580	24	0.42	<5	371	0.27	34	10	21
B380538		3.58	0.44	762	1	0.51	18	520	80	0.81	18	232	0.24	30	20	67
B380539		4.14	0.73	184	1	1.49	27	550	33	0.33	6	439	0.28	35	10	38
B380544		4.71	0.74	181	2	1.08	16	550	23	0.39	7	428	0.27	33	10	31
B380545		4.74	0.66	139	1	1.31	17	570	19	0.38	8	417	0.29	36	10	17
B380546		4.65	0.70	127	2	1.40	18	580	23	0.29	<5	470	0.28	33	<10	18
B380547		4.56	0.75	127	1	1.37	18	570	23	0.41	9	463	0.29	35	<10	18
B380548		4.05	0.73	163	1	1.62	19	570	21	0.38	<5	507	0.30	35	<10	33
B380549																
B380550		2.12	0.57	363	8	0.12	468	310	155	0.02	8	51	0.20	89	30	600
B380551		4.08	0.85	149	2	1.72	19	620	23	0.34	<5	545	0.31	37	<10	31
B380552		4.05	0.84	170	6	1.73	17	560	17	0.35	<5	516	0.29	43	<10	31
B380560		4.06	1.08	252	2	1.70	15	570	15	0.24	<5	530	0.29	53	10	34
B380561		3.92	0.86	234	1	1.68	10	560	13	0.23	5	506	0.28	48	<10	42
B380562		4.30	0.98	242	1	1.82	12	620	19	0.24	<5	506	0.30	51	10	63

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380563		5.92	0.105	<0.5	6.79	1545	1200	2.8	10	4.45	<0.5	8	39	45	2.33	<0.01
B380564		5.50	0.029	<0.5	7.08	593	1200	3.2	<2	2.72	<0.5	7	40	32	2.29	<0.01
B380565		5.92	0.035	<0.5	7.54	404	1280	3.2	<2	3.08	<0.5	6	40	35	2.45	<0.01
B380566		5.52	0.027	<0.5	6.72	608	1200	2.9	<2	3.41	<0.5	9	37	40	2.36	<0.01
B380567		5.70	0.017	<0.5	7.35	425	1360	3.2	<2	2.60	<0.5	9	42	45	2.71	<0.01
B380568		5.74	0.028	<0.5	7.04	1305	1280	3.0	4	2.86	<0.5	8	43	54	2.55	<0.01
B380569		0.04	0.029													
B380570		0.10	0.440	2.6	8.90	<5	1030	1.2	<2	1.47	<0.5	7	11	6960	3.12	0.03
B380575		5.32	0.142	3.1	6.96	4870	910	2.8	16	3.40	9.8	8	32	72	3.19	0.16
B380576		1.74	<0.005	<0.5	0.28	10	20	<0.5	<2	18.95	<0.5	1	4	6	0.18	<0.01
B380577		6.94	0.068	1.0	6.96	2650	1060	3.0	16	3.18	<0.5	6	30	47	2.50	0.02
B380578		3.74	0.066	<0.5	7.32	1850	1200	3.1	7	2.96	<0.5	5	33	49	2.65	0.01
B380579		2.42	0.034	<0.5	6.73	1405	1450	2.9	3	1.97	<0.5	6	36	39	2.48	<0.01
B380587		5.44	0.054	<0.5	6.68	2390	1420	3.3	18	2.56	<0.5	6	25	74	2.11	<0.01
B380588		4.58	0.093	<0.5	7.04	3340	1400	2.9	18	2.34	<0.5	7	28	78	2.07	<0.01
B380589		0.04	0.077													
B380590		0.10	0.442	2.6	9.19	<5	1040	1.2	<2	1.52	<0.5	7	11	7250	3.19	0.03
B380591		5.32	0.072	<0.5	7.67	2820	1550	3.4	12	2.59	<0.5	8	28	76	2.33	<0.01
B380592		6.34	0.086	<0.5	8.03	3200	1610	2.7	19	2.87	<0.5	10	31	92	2.10	0.01
B380593		5.36	0.078	<0.5	8.33	2670	1540	3.4	13	2.19	<0.5	9	32	99	2.62	<0.01
B380594		6.02	0.051	<0.5	8.12	1370	1570	3.3	9	2.40	<0.5	9	28	87	2.33	<0.01
B380595		6.12	0.036	<0.5	8.49	1310	1600	3.2	6	2.92	<0.5	7	28	40	2.95	0.01
B380596		1.52	<0.005	<0.5	0.12	<5	20	<0.5	<2	20.5	<0.5	<1	3	5	0.11	<0.01
B380597		6.02	0.028	<0.5	7.59	1110	1750	2.9	20	1.60	<0.5	9	31	31	2.67	<0.01
B380598		5.96	0.092	<0.5	7.64	3380	1360	3.4	9	1.25	<0.5	8	38	42	2.79	<0.01
B380599		5.86	0.043	<0.5	8.18	1935	1390	3.7	15	1.56	<0.5	8	43	56	2.91	<0.01
B380600		5.46	0.029	<0.5	7.53	1125	1350	3.3	2	2.32	<0.5	8	43	56	2.74	<0.01
B380601		2.90	0.028	<0.5	8.14	1490	1510	3.3	3	2.52	<0.5	10	46	60	3.04	<0.01
B380602		2.76	0.054	<0.5	7.79	917	1470	3.3	5	2.31	<0.5	8	46	55	2.93	0.01
B380603		6.72	0.047	<0.5	8.02	1510	1500	3.6	8	2.61	<0.5	10	47	60	2.88	<0.01
B380604		5.58	0.019	<0.5	8.41	709	1400	3.7	4	2.54	<0.5	8	45	49	2.81	<0.01
B380605		5.42	0.028	<0.5	7.67	510	1220	3.3	3	2.51	<0.5	7	38	61	2.45	<0.01
B380606		5.32	0.019	<0.5	7.15	453	1250	3.2	<2	2.47	<0.5	7	37	39	2.51	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060563

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B380563		3.84	0.92	356	1	1.75	13	560	14	0.24	<5	586	0.28	52	10	34
B380564		3.68	0.99	289	1	1.94	14	560	16	0.17	<5	554	0.28	52	<10	37
B380565		3.69	0.99	284	1	1.92	15	620	17	0.19	<5	591	0.29	52	10	38
B380566		3.74	1.02	278	<1	1.89	12	550	13	0.18	<5	584	0.27	50	<10	34
B380567		3.83	1.09	238	2	2.01	12	630	14	0.22	<5	603	0.31	57	<10	38
B380568		3.87	1.06	263	2	1.60	14	630	15	0.35	<5	520	0.31	57	<10	37
B380569																
B380570		3.55	1.14	451	3	3.35	9	1820	11	0.23	<5	692	0.33	168	<10	55
B380575		3.52	0.68	1025	1	0.35	11	600	453	1.27	64	203	0.25	45	20	1410
B380576		0.06	10.80	158	<1	0.04	5	500	2	0.04	<5	118	0.01	4	<10	9
B380577		3.74	0.68	771	1	0.72	15	610	137	0.35	21	255	0.29	42	10	156
B380578		3.80	0.77	455	3	0.96	15	630	45	0.42	18	345	0.28	45	10	68
B380579		3.70	0.87	245	2	1.41	15	580	23	0.25	5	453	0.29	48	10	45
B380587		4.17	0.66	168	<1	1.51	18	600	19	0.40	<5	451	0.29	35	50	24
B380588		4.61	0.57	158	2	1.13	20	610	24	0.52	<5	378	0.30	39	10	32
B380589																
B380590		3.69	1.16	459	2	3.48	10	1840	12	0.24	<5	719	0.34	173	<10	48
B380591		4.73	0.64	197	<1	1.33	19	650	20	0.48	<5	414	0.32	40	10	17
B380592		4.67	0.72	186	2	1.15	20	690	17	0.46	<5	445	0.33	45	20	19
B380593		4.67	0.88	143	3	1.58	20	660	19	0.49	<5	491	0.32	41	10	16
B380594		4.57	0.84	169	1	1.41	20	640	19	0.37	<5	462	0.32	39	10	18
B380595		4.20	0.95	318	<1	1.17	20	720	34	0.31	6	456	0.34	43	10	70
B380596		0.04	12.50	167	<1	0.01	5	580	<2	0.01	<5	118	<0.01	2	<10	9
B380597		3.77	0.97	254	<1	1.37	21	720	32	0.18	7	489	0.34	42	10	62
B380598		4.04	1.04	189	<1	1.61	14	660	27	0.35	<5	482	0.31	49	10	39
B380599		4.19	1.19	204	<1	1.68	14	690	27	0.30	<5	521	0.32	55	10	40
B380600		4.11	1.16	250	<1	1.70	13	690	26	0.31	<5	540	0.32	54	10	35
B380601		4.19	1.33	277	2	1.82	13	780	22	0.35	<5	597	0.35	60	10	36
B380602		3.96	1.28	264	1	1.78	14	750	25	0.32	<5	580	0.34	60	10	38
B380603		4.28	1.26	274	<1	1.88	13	730	25	0.30	<5	575	0.35	57	<10	37
B380604		4.16	1.33	301	<1	1.82	13	690	24	0.22	<5	556	0.33	55	10	39
B380605		4.39	1.10	294	<1	1.72	12	610	29	0.28	<5	472	0.28	48	10	41
B380606		3.76	1.02	288	<1	1.80	12	600	25	0.45	<5	510	0.29	45	10	33

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da -AUG-2005
Account: STRGOL

CERTIFICATE VA05060567

Project: Dublin Gulch-1735

P.O. No.:

This report is for 95 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 21-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES
Au-GRA21	Au 30g FA-GRAV finish	WST-SIM

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381725		4.62	0.508		<0.5	4.25	1545	460	1.0	43	0.89	<0.5	9	192	22	1.85
B381726		1.24	0.064		<0.5	6.78	463	930	1.5	<2	1.15	<0.5	9	131	17	2.37
B381727		1.94	0.076		<0.5	8.09	604	1380	2.7	3	2.90	<0.5	11	137	19	3.25
B381728		3.44	0.081		<0.5	7.89	378	1440	2.5	5	2.31	<0.5	9	101	46	3.04
B381729		0.04	0.098													
B381730		0.12	1.415		<0.5	7.12	1240	720	6.3	<2	0.01	<0.5	4	201	38	3.81
B381731		2.92	0.095		<0.5	8.03	682	1460	2.9	2	2.87	<0.5	10	103	25	3.22
B381732		4.56	0.200		<0.5	6.97	1275	1360	2.8	8	2.36	<0.5	12	163	38	2.66
B381733		0.84	0.073		<0.5	4.46	650	490	1.4	<2	3.16	<0.5	9	145	15	1.38
B381734		3.70	0.041		<0.5	7.06	371	1460	2.3	<2	2.54	<0.5	11	154	28	3.15
B381735		4.08	1.085		<0.5	8.00	718	1460	2.0	82	3.05	<0.5	16	100	33	2.57
B381736		0.48	<0.005		<0.5	0.09	5	10	<0.5	<2	19.45	<0.5	<1	7	1	0.08
B381737		5.46	2.15		<0.5	7.99	692	1400	2.3	5	2.86	<0.5	12	138	26	3.36
B381738		4.96	1.775		<0.5	6.97	2050	1270	2.0	190	3.46	<0.5	28	163	24	3.29
B381739		5.00	0.025		<0.5	7.55	161	1350	2.1	<2	2.50	<0.5	11	140	13	3.65
B381740		4.44	0.084		<0.5	8.49	604	1450	2.3	<2	2.81	<0.5	17	181	19	3.74
B381764		2.68	0.547		<0.5	7.72	1010	1250	2.2	36	2.61	<0.5	12	150	42	3.14
B381765		2.52	0.049		<0.5	7.98	141	1410	2.5	2	2.48	<0.5	14	180	29	3.57
B381766		5.26	0.078		<0.5	7.78	917	1370	2.5	4	2.58	<0.5	15	154	32	3.45
B381767		2.20	0.165		<0.5	8.01	761	1280	2.7	6	3.26	<0.5	12	162	61	3.12
B381768		3.58	0.248		<0.5	7.65	312	1440	2.5	13	2.55	<0.5	11	137	75	2.88
B381769		0.04	0.236													
B381770		0.12	4.34		8.7	7.87	14	480	0.9	<2	2.81	1.4	19	23	122	4.29
B381771		5.34	0.056		<0.5	8.01	105	1490	3.2	5	2.60	<0.5	13	145	27	3.35
B381772		5.76	0.042		<0.5	8.58	190	1540	3.1	4	2.88	<0.5	12	181	35	3.24
B381773		5.70	0.136		<0.5	8.26	409	1440	2.9	10	3.05	<0.5	10	132	60	2.86
B381781		2.94	0.928		<0.5	7.77	872	1590	2.5	33	2.42	<0.5	14	156	135	2.75
B381782		2.66	0.987		<0.5	8.06	839	1530	2.5	48	2.36	<0.5	17	104	169	2.81
B381783		6.48	0.074		<0.5	8.11	401	1550	3.0	5	2.68	<0.5	9	162	59	2.99
B381784		6.48	0.112		<0.5	7.87	409	1430	3.2	3	3.14	<0.5	9	113	72	2.99
B381789		0.04	0.139													
B381790		0.12	0.933		2.1	8.31	10	460	0.7	<2	1.99	1.0	23	104	2060	5.35
B381791		5.72	0.250		<0.5	7.29	724	1390	2.6	10	2.49	<0.5	8	99	44	2.22
B381792		6.18	0.221		<0.5	7.26	1440	1430	2.7	8	2.29	<0.5	10	134	39	2.09
B381793		6.20	0.081		<0.5	7.76	222	1570	2.9	2	2.31	<0.5	8	96	34	2.41
B381798		6.46	0.434		<0.5	7.58	237	1540	2.8	14	2.13	<0.5	8	160	34	2.38
B381799		6.74	0.151		<0.5	7.81	254	1510	2.9	2	1.75	<0.5	8	104	35	2.54
B381800		2.70	0.120		<0.5	8.43	142	1640	3.0	12	2.15	<0.5	7	140	42	2.55
B381801		1.24	1.135		0.7	7.75	192	1180	2.8	31	2.38	<0.5	10	106	38	2.11
B381802		1.22	0.451		0.5	7.85	230	1260	2.9	16	2.85	<0.5	11	136	41	2.41

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B381725		<0.01	1.84	0.37	183	1	0.42	14	160	5	0.05	<5	76	0.20	35	20
B381726		0.01	2.70	0.67	225	1	0.60	20	330	10	0.01	<5	133	0.30	55	20
B381727		0.01	2.60	1.32	353	2	1.35	16	780	15	0.01	<5	434	0.38	60	10
B381728		<0.01	3.33	1.17	325	1	1.22	19	710	14	0.02	<5	394	0.34	63	10
B381729																
B381730		0.05	2.80	0.34	88	3	0.11	17	320	27	0.01	115	92	0.31	88	10
B381731		0.01	3.01	1.27	349	1	1.42	14	810	14	0.04	<5	507	0.37	58	20
B381732		<0.01	3.53	1.08	231	1	1.30	16	760	12	0.06	<5	428	0.36	61	10
B381733		0.01	1.92	0.45	201	1	0.74	11	430	7	0.01	<5	142	0.18	35	20
B381734		0.01	3.14	1.22	358	1	1.41	31	720	13	0.04	<5	422	0.38	86	10
B381735		<0.01	5.25	1.26	507	2	0.98	27	740	16	0.04	5	378	0.39	83	10
B381736		<0.01	0.02	11.40	126	<1	0.01	3	450	2	0.01	<5	108	<0.01	2	<10
B381737		<0.01	3.70	1.47	424	4	1.40	38	780	19	0.05	<5	396	0.43	108	10
B381738		<0.01	3.40	1.38	320	4	1.08	49	730	21	0.10	5	332	0.39	104	30
B381739		<0.01	2.99	1.64	397	2	1.01	40	790	22	0.04	<5	333	0.42	108	10
B381740		0.01	3.43	1.49	396	4	1.56	41	830	24	0.05	<5	395	0.45	111	20
B381764		<0.01	3.20	1.23	261	3	1.38	35	710	19	0.21	5	328	0.37	91	90
B381765		0.01	2.99	1.40	367	3	1.65	42	720	22	0.16	<5	432	0.40	100	10
B381766		<0.01	3.56	1.38	380	2	1.62	44	750	21	0.18	<5	424	0.42	108	10
B381767		0.01	3.24	1.28	358	4	1.42	44	790	15	0.24	7	365	0.39	108	40
B381768		0.01	4.16	1.19	273	8	1.56	25	670	19	0.27	<5	461	0.33	71	20
B381769																
B381770		0.01	2.36	1.35	957	13	1.77	13	920	25	0.69	<5	411	0.37	153	<10
B381771		<0.01	3.34	1.37	390	3	1.84	29	770	19	0.11	<5	521	0.37	84	10
B381772		<0.01	3.40	1.38	353	2	1.87	28	740	12	0.16	<5	538	0.39	82	<10
B381773		0.01	3.37	1.20	280	3	1.80	17	690	17	0.23	<5	559	0.30	54	20
B381781		<0.01	4.77	1.19	245	3	1.66	17	710	17	0.30	<5	521	0.31	55	30
B381782		<0.01	4.67	1.19	242	3	1.60	22	700	19	0.37	<5	524	0.31	54	20
B381783		<0.01	3.67	1.28	299	2	1.92	15	700	19	0.27	<5	609	0.32	56	30
B381784		<0.01	3.25	1.32	283	1	1.72	29	680	13	0.29	6	528	0.33	69	20
B381789																
B381790		<0.01	1.87	1.38	439	3	3.48	54	680	20	0.64	<5	217	0.32	94	<10
B381791		<0.01	4.10	0.68	251	4	1.42	23	600	24	0.17	21	368	0.28	36	20
B381792		0.01	4.28	0.58	238	3	1.40	20	610	30	0.23	16	345	0.26	34	20
B381793		0.01	3.98	0.70	261	3	1.50	20	610	28	0.19	10	415	0.29	36	20
B381798		0.04	3.94	0.77	278	3	1.33	20	620	48	0.20	25	358	0.28	35	20
B381799		0.03	3.91	0.81	262	2	1.34	24	640	42	0.28	24	323	0.30	38	10
B381800		0.03	4.19	0.76	298	3	1.38	22	660	53	0.36	26	337	0.30	38	10
B381801		0.07	3.74	0.59	313	2	1.32	22	590	84	0.36	43	273	0.27	34	20
B381802		0.01	3.86	0.58	373	3	1.31	19	630	47	0.89	38	273	0.27	35	20

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

(: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B381725		18
B381726		34
B381727		47
B381728		51
B381729		
B381730		46
B381731		51
B381732		35
B381733		20
B381734		73
B381735		48
B381736		7
B381737		81
B381738		60
B381739		83
B381740		88
B381764		62
B381765		84
B381766		86
B381767		83
B381768		53
B381769		
B381770		103
B381771		74
B381772		66
B381773		37
B381781		32
B381782		34
B381783		41
B381784		35
B381789		
B381790		209
B381791		47
B381792		44
B381793		60
B381798		57
B381799		81
B381800		59
B381801		76
B381802		66

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method	WEI-21	Au-AA23	Au-GRA21	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Recvd Wt.	Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe
	Units	kg	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%
	LOR	0.02	0.005	0.05	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01
B381803		6.14	4.77		1.5	7.14	233	1380	2.5	122	1.72	<0.5	8	122	35	2.14
B381804		5.94	0.469		1.1	8.26	872	1530	3.1	82	2.37	<0.5	9	135	27	2.44
B381805		5.32	0.720		1.2	6.71	410	1090	2.5	35	1.91	0.6	9	136	72	2.30
B381806		0.90	7.09		9.4	0.66	3060	60	<0.5	244	3.18	<0.5	86	249	741	5.60
B381807		1.48	2.59		2.2	6.78	1030	580	2.3	38	0.84	<0.5	12	127	121	3.47
B381808		1.28	>10.0	14.25	11.2	2.39	2850	230	0.8	663	3.28	0.5	34	230	92	1.52
B381809		0.04	>10.0	16.05												
B381810		0.10	4.74		8.9	8.23	22	490	0.9	<2	2.89	1.5	18	22	127	4.41
B381811		3.48	2.14		2.2	6.99	2150	530	2.2	60	2.35	6.7	13	166	107	2.68
B381812		3.18	>10.0	14.25	10.0	5.20	>10000	240	2.0	377	1.91	10.4	321	140	71	5.70
B381813		6.00	5.57		3.2	7.35	7640	640	2.9	165	2.38	2.5	49	86	107	2.97
B381819		6.72	0.219		0.6	7.54	743	950	2.6	10	1.95	1.2	7	23	48	2.46
B381820		3.10	1.210		2.1	4.26	2740	510	1.7	38	2.17	0.7	19	83	114	2.66
B381821		1.26	0.030		<0.5	7.85	289	1540	3.1	<2	2.69	<0.5	10	32	48	2.24
B381822		1.36	0.025		<0.5	7.97	117	1620	3.2	<2	2.75	<0.5	8	66	16	2.85
B381823		6.38	0.103		<0.5	7.17	159	1580	2.8	6	2.18	<0.5	7	27	39	2.22
B381832		6.52	0.126		1.1	7.21	378	760	2.6	<2	2.69	1.5	7	53	31	2.26
B381833		5.48	0.143		1.1	7.22	236	820	2.7	3	2.85	1.2	9	20	37	2.42
B381834		6.12	0.394		1.3	6.50	354	900	2.6	12	2.42	3.1	7	49	31	2.13
B381839		4.74	0.138		<0.5	7.31	103	1590	3.0	<2	2.23	<0.5	8	25	24	2.46
B381840		7.80	1.390		<0.5	7.35	385	1520	2.8	17	2.05	<0.5	13	66	52	2.37
B381841		2.98	0.581		<0.5	7.83	342	1680	3.0	19	2.26	<0.5	11	29	59	2.59
B381845		4.84	0.265		<0.5	7.30	527	1480	3.0	5	1.96	<0.5	10	74	36	2.48
B381846		6.44	0.644		<0.5	7.15	514	1600	2.6	19	2.21	<0.5	11	24	75	2.44
B381847		6.24	0.569		1.1	11.45	770	690	5.4	13	4.87	4.2	16	124	94	5.32
B381848		1.72	0.196		1.0	6.96	118	450	2.6	2	3.53	3.5	7	18	48	2.91
B381849		0.04	0.116													
B381850		0.10	0.443		2.5	9.41	<5	1070	1.2	<2	1.56	<0.5	9	9	7420	3.36
B381851		4.26	0.120		<0.5	7.93	365	1580	3.2	<2	1.81	<0.5	9	26	50	2.44
B381852		6.00	0.301		<0.5	7.83	199	1530	3.1	3	1.85	<0.5	7	65	37	2.64
B381853		5.68	0.123		<0.5	8.13	161	1710	3.4	<2	1.51	<0.5	10	30	41	2.86
B381854		3.74	0.697		<0.5	7.99	50	1760	3.5	18	1.25	<0.5	9	73	44	3.10
B381855		2.86	1.535		<0.5	8.32	97	380	3.2	14	1.09	<0.5	9	27	39	3.51
B381856		1.98	<0.005		<0.5	0.18	7	20	<0.5	<2	19.25	<0.5	<1	4	2	0.13
B381857		5.40	0.136		<0.5	7.89	63	1470	2.7	14	2.54	<0.5	7	24	31	2.72
B381858		2.76	0.431		<0.5	7.34	798	1500	2.7	9	2.22	<0.5	12	40	52	2.28
B381859		1.88	4.68		3.4	7.63	319	1120	3.2	115	1.16	0.7	9	24	72	1.65
B381860		5.22	0.557		<0.5	7.75	161	1600	3.1	12	1.33	<0.5	7	55	93	3.34
B381861		1.52	0.844		<0.5	7.24	41	1450	2.6	9	2.59	<0.5	7	24	37	2.57
B381862		1.16	4.95		<0.5	7.21	45	1420	2.8	63	1.98	<0.5	6	48	56	2.70

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B381803		0.01	3.56	0.71	258	4	1.14	21	550	130	0.22	63	272	0.25	32	20
B381804		0.02	4.15	0.76	334	4	1.42	23	650	111	0.15	49	380	0.31	38	20
B381805		0.02	3.69	0.60	296	4	0.67	22	570	112	0.52	61	197	0.25	33	20
B381806		0.02	0.27	0.10	325	14	0.01	44	30	812	5.62	243	76	0.01	2	10
B381807		0.02	3.83	0.76	115	2	0.50	19	470	122	1.51	44	174	0.18	26	20
B381808		0.02	1.18	0.20	511	4	0.05	14	200	876	0.85	334	92	0.06	11	30
B381809																
B381810		0.03	2.44	1.40	985	14	1.84	13	950	25	0.71	<5	429	0.38	156	<10
B381811		0.09	3.30	0.38	464	5	0.03	18	510	384	2.16	126	66	0.19	29	60
B381812		<0.01	2.51	0.37	367	16	0.03	78	430	1240	3.52	351	52	0.15	24	50
B381813		0.01	3.49	0.45	431	6	0.06	26	530	487	1.64	130	74	0.23	32	50
B381819		0.03	3.78	0.65	423	4	0.55	18	570	176	0.84	41	145	0.25	33	30
B381820		0.02	2.08	0.28	454	5	0.11	22	340	221	1.70	77	88	0.15	20	20
B381821		0.02	4.22	0.43	482	2	1.03	27	690	29	0.20	25	250	0.33	47	20
B381822		0.01	4.12	0.54	491	2	0.98	21	660	30	0.12	21	286	0.31	39	20
B381823		0.02	4.36	0.53	366	4	1.11	20	590	36	0.21	25	305	0.28	35	20
B381832		0.04	3.61	0.72	799	3	0.22	18	570	148	0.20	11	166	0.26	33	30
B381833		0.04	3.68	0.68	823	4	0.31	21	550	143	0.43	13	194	0.25	33	30
B381834		0.07	3.54	0.47	708	7	0.31	17	550	264	0.48	13	146	0.23	29	20
B381839		0.01	3.68	0.86	302	2	1.66	21	630	28	0.08	<5	518	0.31	37	20
B381840		0.01	4.01	0.79	263	4	1.58	21	590	28	0.17	6	463	0.30	36	20
B381841		0.01	4.08	0.89	268	2	1.69	22	670	25	0.20	<5	507	0.33	40	40
B381845		0.01	3.89	0.81	283	1	1.56	21	590	27	0.18	6	438	0.30	37	20
B381846		0.01	4.24	0.87	277	8	1.16	22	600	31	0.22	12	433	0.29	35	20
B381847		0.01	7.84	0.74	723	4	1.46	37	1060	177	2.85	42	465	0.43	64	30
B381848		0.08	3.59	0.34	502	1	0.34	15	470	123	2.04	26	200	0.21	28	20
B381849																
B381850		0.03	3.89	1.16	486	3	3.68	10	1960	11	0.24	<5	686	0.34	180	<10
B381851		0.02	4.06	0.63	259	2	1.48	19	640	28	0.20	11	367	0.29	37	10
B381852		0.02	3.88	0.79	292	2	1.48	20	590	29	0.20	12	405	0.30	37	10
B381853		0.01	3.82	0.87	251	2	1.56	22	670	28	0.13	10	441	0.33	40	10
B381854		0.01	3.82	0.97	242	7	1.54	23	700	30	0.07	8	450	0.35	43	10
B381855		0.03	3.84	0.47	140	8	1.07	24	680	49	2.18	40	225	0.31	39	20
B381856		<0.01	0.05	11.40	138	<1	0.03	3	580	2	0.02	<5	110	0.01	3	<10
B381857		0.02	3.85	0.85	386	2	0.92	19	650	33	0.17	18	358	0.30	37	20
B381858		0.01	4.14	0.60	338	3	0.79	17	600	60	0.30	27	298	0.27	35	10
B381859		0.02	4.03	0.45	155	1	0.53	18	640	543	0.71	135	158	0.26	37	20
B381860		0.02	4.31	0.92	254	2	1.05	19	670	34	0.32	19	381	0.31	40	20
B381861		0.01	3.98	0.96	382	3	0.78	16	590	28	0.13	18	426	0.28	38	20
B381862		0.01	3.82	0.95	325	2	0.81	17	600	25	0.11	16	418	0.29	37	20

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B381803		73
B381804		118
B381805		124
B381806		39
B381807		49
B381808		22
B381809		
B381810		105
B381811		1160
B381812		1790
B381813		465
B381819		233
B381820		114
B381821		79
B381822		73
B381823		65
B381832		275
B381833		230
B381834		525
B381839		64
B381840		57
B381841		54
B381845		58
B381846		46
B381847		798
B381848		611
B381849		
B381850		52
B381851		50
B381852		61
B381853		64
B381854		62
B381855		128
B381856		8
B381857		78
B381858		91
B381859		118
B381860		42
B381861		44
B381862		42

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-GRA21 Au ppm 0.05	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381863		5.76	0.470		<0.5	7.34	234	1350	2.7	8	2.88	<0.5	11	27	41	2.42
B381864		6.16	0.360		0.6	7.11	154	1320	2.8	6	2.06	<0.5	8	58	51	2.25
B381865		5.08	0.532		<0.5	7.40	362	1350	2.9	13	2.03	<0.5	10	32	56	2.50
B381866		6.40	2.24		<0.5	7.08	354	1310	2.4	93	2.06	<0.5	10	66	75	2.48
B381872		6.10	0.593		<0.5	6.99	252	1250	2.7	10	2.59	<0.5	13	36	42	2.62
B381873		6.30	0.202		<0.5	7.39	442	1270	3.2	6	3.33	<0.5	13	56	50	2.64
B381874		6.30	0.246		<0.5	7.61	150	1350	3.2	3	3.23	<0.5	11	44	56	2.86
B381875		5.90	0.329		<0.5	7.83	110	1300	3.0	5	2.43	<0.5	12	67	92	2.99
B381876		2.22	<0.005		<0.5	0.18	9	20	<0.5	<2	18.75	<0.5	<1	4	3	0.12
B381877		5.58	0.373		<0.5	7.30	28	1270	3.0	<2	2.68	<0.5	11	70	42	2.90
B381878		6.26	0.319		<0.5	7.11	19	1090	3.1	3	3.03	<0.5	12	56	27	2.86
B382076		1.50	<0.005		<0.5	0.13	5	20	<0.5	<2	18.90	<0.5	<1	4	3	0.11
B382077		1.94	0.130		<0.5	7.17	6240	1440	2.4	19	3.11	<0.5	8	21	49	2.24
B382078		3.28	0.040		<0.5	7.55	1510	1470	3.2	3	1.81	<0.5	6	49	68	2.23
B382079		3.56	0.021		<0.5	7.29	1990	1200	4.6	2	2.50	<0.5	4	24	67	1.69

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B381863		0.02	3.74	1.07	349	4	0.82	18	610	24	0.21	11	463	0.29	42	20
B381864		0.02	4.05	1.00	234	3	1.10	16	580	24	0.21	<5	454	0.27	38	20
B381865		0.01	4.32	0.97	234	1	1.50	16	600	29	0.26	<5	458	0.28	43	10
B381866		0.02	3.99	0.95	203	2	1.25	15	590	20	0.37	6	427	0.26	41	20
B381872		0.01	3.85	1.43	387	3	0.84	19	650	36	0.20	18	501	0.30	48	20
B381873		0.02	3.87	1.19	390	3	1.68	23	690	25	0.24	11	536	0.33	55	20
B381874		0.02	3.87	1.23	379	3	1.97	23	730	19	0.24	<5	559	0.36	57	<10
B381875		0.01	4.14	1.40	295	2	1.88	21	690	17	0.34	<5	510	0.34	57	10
B381876		<0.01	0.05	10.90	146	1	0.02	5	500	<2	0.01	<5	101	0.01	3	<10
B381877		0.01	3.50	1.38	361	2	1.91	22	670	18	0.16	6	498	0.32	54	<10
B381878		0.01	3.73	1.46	410	2	1.90	30	660	15	0.10	7	476	0.35	57	<10
B382076		<0.01	0.04	10.90	154	<1	0.02	4	470	<2	0.01	<5	108	0.01	3	<10
B382077		0.01	4.64	0.86	187	4	0.76	16	560	20	0.43	9	463	0.26	31	40
B382078		<0.01	3.92	0.72	133	2	1.42	19	620	18	0.38	<5	435	0.29	36	10
B382079		0.01	3.54	0.72	102	2	1.74	9	430	17	0.43	<5	393	0.16	35	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 4-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060567

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B381863		45
B381864		30
B381865		38
B381866		29
B381872		66
B381873		48
B381874		40
B381875		48
B381876		9
B381877		39
B381878		45
B382076		7
B382077		27
B382078		26
B382079		27

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05060237

Project: Dublin Gulch-1735

P.O. No.:

This report is for 74 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 21-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B381879		3.90	0.022		<0.5	7.23	180	1140	2.2	2	1.96	<0.5	8	75	20	2.89
B381880		2.34	0.105		<0.5	7.84	192	990	2.2	4	2.06	<0.5	7	39	20	2.53
B381881		0.56	0.049		<0.5	8.02	656	1320	2.6	<2	2.59	<0.5	10	73	26	3.21
B381882		0.86	0.023		<0.5	7.63	332	1270	2.5	<2	2.53	<0.5	9	56	18	3.26
B381883		0.64	1.900		<0.5	6.36	734	1130	1.5	53	1.03	<0.5	7	57	9	1.60
B381884		0.88	0.088		<0.5	7.45	898	1320	2.5	5	1.98	<0.5	9	46	16	2.66
B381885		2.98	0.152		<0.5	8.04	1075	1220	2.3	13	1.75	<0.5	6	64	13	2.37
B381886		4.04	0.128		<0.5	7.95	621	1150	2.3	6	1.96	<0.5	8	55	21	2.94
B381887		2.56	0.061		<0.5	8.26	604	1380	2.6	7	2.56	<0.5	12	83	24	3.68
B381893		3.72	0.034		<0.5	7.49	102	1340	2.4	2	2.50	<0.5	10	64	12	3.35
B381894		3.94	0.011		<0.5	7.88	248	1330	2.4	<2	2.46	<0.5	11	83	11	3.51
B381895		3.78	0.249		<0.5	7.76	942	1310	2.3	20	2.16	<0.5	11	67	28	3.22
B381896		2.08	<0.005		<0.5	0.13	<5	20	<0.5	<2	19.10	<0.5	2	4	2	0.13
B381900		4.70	0.567		<0.5	8.33	705	1440	2.4	52	2.82	<0.5	16	74	14	3.72
B381901		2.00	0.155		<0.5	8.19	249	1460	2.5	3	2.65	<0.5	12	86	14	3.67
B381902		1.30	0.109		<0.5	7.76	319	1380	2.4	3	2.66	<0.5	12	66	18	3.49
B381903		1.42	0.013		<0.5	8.68	244	1450	2.6	2	2.42	<0.5	13	89	9	3.87
B381904		1.42	0.252		<0.5	8.20	217	1440	2.5	11	2.51	<0.5	11	69	22	3.67
B381905		4.44	0.410		<0.5	8.12	787	1380	2.5	29	2.59	<0.5	14	86	19	3.50
B381906		4.96	0.251	0.152	<0.5	8.31	130	1390	2.4	14	2.67	<0.5	12	69	16	3.58
B381907		5.94	0.257		<0.5	8.05	297	1370	2.5	16	2.62	<0.5	13	82	17	3.46
B381908		3.78	1.185		<0.5	7.41	318	1350	2.3	83	2.33	<0.5	12	69	9	3.48
B381909		<0.02	1.050													
B381910		0.10	2.86		<0.5	7.42	2120	720	13.4	<2	0.02	<0.5	<1	140	102	3.36
B381911		1.66	0.079		<0.5	7.84	439	1320	2.5	8	2.16	<0.5	11	85	14	3.35
B381912		1.30	0.248		<0.5	7.62	418	1270	2.2	18	2.09	<0.5	9	62	15	3.22
B381913		1.46	0.011		<0.5	7.97	194	1400	2.3	<2	2.58	<0.5	12	83	12	3.45
B381919		2.48	0.025		<0.5	8.50	238	1440	2.4	2	2.64	<0.5	12	73	15	3.67
B381920		3.70	0.049		<0.5	8.57	482	1520	2.4	8	2.52	<0.5	11	92	21	3.79
B381921		1.60	0.023		<0.5	8.34	214	1520	2.4	<2	2.60	<0.5	10	61	16	3.49
B381922		1.26	0.013		<0.5	7.12	266	1390	2.2	<2	2.40	<0.5	9	80	17	3.19
B381923		2.44	0.201		<0.5	7.64	980	1350	2.3	10	2.32	<0.5	13	58	61	3.06
B381924		3.22	0.033		<0.5	7.27	414	1330	2.8	3	2.54	<0.5	8	67	35	2.78
B381925		2.44	<0.005		<0.5	7.73	68	1350	2.6	<2	2.52	<0.5	11	62	14	3.23
B381926		3.28	0.181		<0.5	8.16	217	1420	2.6	32	2.43	<0.5	9	82	16	3.32
B382099		6.52	0.072		<0.5	7.70	2180	1560	3.0	12	2.23	<0.5	7	32	41	2.51
B382100		6.02	0.061		<0.5	7.53	5660	1540	2.7	10	3.24	<0.5	6	52	36	2.68
B382101		2.50	0.018		<0.5	7.45	925	1510	3.0	3	2.20	<0.5	7	29	33	2.42
B382102		2.40	0.020		<0.5	7.49	968	1550	3.0	3	2.24	<0.5	6	48	35	2.47
B382103		1.78	0.013		<0.5	7.32	139	1610	3.1	2	2.37	<0.5	7	28	23	2.49

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B381879		<0.01	2.92	1.12	334	<1	1.58	27	620	25	0.01	<5	340	0.36	84	10
B381880		0.01	3.06	0.94	264	<1	1.66	18	530	29	0.01	5	358	0.30	61	10
B381881		0.01	2.98	1.28	350	<1	1.66	28	760	22	0.02	<5	425	0.40	93	10
B381882		0.01	2.72	1.24	378	<1	1.60	29	720	22	0.01	<5	420	0.40	90	10
B381883		0.01	3.52	0.59	113	<1	1.02	12	370	20	0.02	6	254	0.19	37	<10
B381884		0.01	3.68	1.06	236	1	1.54	24	650	26	0.02	<5	359	0.35	77	10
B381885		0.01	4.03	0.91	221	<1	1.45	20	580	22	0.02	5	339	0.30	64	30
B381886		0.01	3.86	1.14	297	1	1.55	29	680	26	0.02	<5	348	0.37	89	10
B381887		<0.01	3.05	1.46	416	1	1.65	38	800	23	0.05	<5	428	0.47	112	10
B381893		0.01	2.80	1.28	435	<1	1.56	35	790	25	0.01	<5	417	0.41	98	<10
B381894		0.01	2.74	1.38	431	<1	1.61	38	790	25	<0.01	<5	403	0.43	104	10
B381895		0.01	3.30	1.32	318	1	1.48	34	760	16	0.02	<5	370	0.42	105	20
B381896		<0.01	0.03	11.00	176	<1	0.02	4	490	<2	0.01	<5	101	0.01	3	<10
B381900		0.01	2.95	1.52	457	1	1.64	42	820	23	0.07	<5	435	0.47	114	<10
B381901		0.02	3.06	1.49	421	1	1.66	38	830	20	0.02	<5	415	0.46	112	20
B381902		0.02	2.99	1.42	424	1	1.64	35	790	19	0.03	<5	396	0.45	110	20
B381903		0.01	2.82	1.56	475	<1	1.66	42	860	23	<0.01	<5	407	0.48	116	10
B381904		0.01	3.03	1.45	450	1	1.62	39	810	18	0.01	<5	428	0.46	110	30
B381905		<0.01	3.36	1.43	429	2	1.61	40	770	20	0.07	<5	425	0.45	110	<10
B381906		<0.01	2.80	1.46	470	1	1.58	38	790	20	0.04	<5	429	0.45	108	<10
B381907		0.01	3.15	1.43	420	2	1.62	37	770	21	0.04	<5	419	0.44	108	10
B381908		<0.01	3.00	1.35	441	<1	1.48	36	790	21	0.01	<5	386	0.43	106	10
B381909																
B381910		0.06	3.10	0.37	71	2	0.09	10	320	27	0.02	151	136	0.27	104	20
B381911		0.01	2.95	1.34	381	<1	1.50	37	770	18	0.01	<5	382	0.42	100	10
B381912		0.01	3.07	1.30	355	<1	1.38	33	720	17	0.01	5	355	0.39	95	20
B381913		0.01	3.02	1.39	448	<1	1.56	36	770	18	0.01	<5	428	0.44	105	20
B381919		0.01	3.21	1.46	466	<1	1.62	38	820	20	0.02	<5	448	0.46	110	20
B381920		0.01	3.34	1.50	418	1	1.61	37	860	19	0.02	<5	443	0.46	113	10
B381921		0.01	3.11	1.38	420	1	1.66	30	770	14	0.02	<5	468	0.42	96	10
B381922		0.01	3.00	1.22	384	1	1.55	30	720	16	0.01	<5	427	0.40	93	10
B381923		0.01	3.24	1.18	318	1	1.49	27	670	19	0.11	7	439	0.36	78	10
B381924		<0.01	3.00	1.08	355	1	1.60	18	640	15	0.09	<5	490	0.31	58	<10
B381925		<0.01	3.09	1.23	461	<1	1.58	31	690	23	0.01	<5	433	0.38	90	<10
B381926		<0.01	3.35	1.30	406	<1	1.54	31	710	19	0.01	<5	430	0.38	87	10
B382099		0.01	3.70	0.80	203	3	1.50	19	640	14	0.37	7	484	0.31	37	40
B382100		<0.01	3.58	0.77	233	1	1.42	20	600	15	0.47	<5	494	0.30	36	10
B382101		0.01	3.53	0.80	218	2	1.40	20	620	16	0.29	<5	455	0.31	37	20
B382102		0.01	3.53	0.80	221	1	1.46	21	650	14	0.30	<5	472	0.32	38	20
B382103		0.01	3.58	0.81	274	1	1.40	20	660	21	0.22	<5	479	0.32	39	20

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

094876

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B381879		65
B381880		52
B381881		65
B381882		69
B381883		18
B381884		46
B381885		37
B381886		56
B381887		80
B381893		89
B381894		86
B381895		63
B381896		4
B381900		93
B381901		89
B381902		86
B381903		109
B381904		101
B381905		95
B381906		96
B381907		88
B381908		94
B381909		
B381910		14
B381911		84
B381912		76
B381913		91
B381919		98
B381920		86
B381921		86
B381922		78
B381923		53
B381924		57
B381925		91
B381926		84
B382099		23
B382100		24
B382101		24
B382102		25
B382103		34

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method	WEI-21	Au-AA23	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Recvd Wt.	Au	Au Check	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe
	Units	kg	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%
	LOR	0.02	0.005	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01
B382104		6.40	0.028		<0.5	7.00	1050	1520	3.0	4	2.03	<0.5	5	55	33	2.34
B382105		6.00	0.028		<0.5	7.41	1245	1630	3.0	3	2.75	<0.5	7	29	43	2.42
B382106		2.74	0.095		<0.5	7.36	8950	1580	2.9	8	1.95	<0.5	5	50	28	2.74
B382107		3.30	0.071		<0.5	7.03	2700	1390	3.1	6	2.21	<0.5	5	23	33	1.94
B382108		6.32	0.100		<0.5	6.94	1980	1500	3.2	14	1.99	<0.5	6	50	27	2.23
B382109		<0.02	0.108													
B382110		0.10	0.979		2.0	7.63	20	450	0.7	<2	1.92	0.8	23	101	2070	5.17
B382111		4.78	0.029		<0.5	6.82	1400	1450	2.9	3	2.25	<0.5	5	24	32	2.29
B382112		3.10	0.249		<0.5	7.45	9950	1570	2.2	9	2.38	<0.5	7	39	35	2.52
B382113		4.44	0.032		<0.5	7.61	1775	1650	3.3	4	1.98	<0.5	7	26	41	2.52
B382114		2.24	0.045		<0.5	7.24	1580	1610	3.2	9	1.71	<0.5	6	47	42	2.35
B382115		3.28	0.262		0.5	6.68	>10000	1230	2.3	7	2.76	<0.5	12	22	49	3.31
B382125		4.94	0.021		<0.5	7.79	1475	1450	3.3	4	2.24	<0.5	6	44	24	2.33
B382126		3.80	0.018		<0.5	8.03	891	1550	3.3	2	2.17	<0.5	6	26	41	2.51
B382127		3.96	0.125		<0.5	7.06	4170	1470	2.7	11	2.52	<0.5	5	49	39	2.20
B382128		4.98	0.028		<0.5	7.39	1350	1600	3.1	7	2.34	<0.5	6	28	29	2.48
B382129		<0.02	0.028													
B382130		0.10	0.435		2.3	8.88	9	1040	1.2	<2	1.50	<0.5	8	11	7390	3.24
B382131		3.52	0.128		<0.5	7.26	4220	1410	2.6	14	1.96	<0.5	7	44	54	2.24
B382132		2.54	0.350		2.4	6.75	>10000	810	2.7	13	3.06	1.0	9	19	209	3.71
B382133		5.28	0.069		<0.5	7.93	4420	1520	2.8	7	2.80	<0.5	8	52	43	2.53
B382134		3.32	0.078		<0.5	7.18	3080	1510	2.4	14	2.90	<0.5	6	25	35	2.06
B382135		2.64	0.042		<0.5	7.20	1705	1440	2.8	6	2.54	<0.5	5	43	45	1.92
B382136		1.92	<0.005		<0.5	0.13	10	20	<0.5	<2	19.50	<0.5	<1	1	2	0.13
B382137		1.96	0.090		<0.5	7.39	4210	1510	2.1	18	1.87	<0.5	6	48	34	1.90
B382138		3.82	0.180		<0.5	7.31	5450	1180	2.6	18	2.68	<0.5	7	25	53	2.42
B382139		5.00	0.128		<0.5	7.09	5410	1500	2.7	24	2.44	<0.5	6	47	30	2.50
B382145		3.90	0.168		<0.5	7.13	>10000	1400	2.2	29	2.41	<0.5	6	24	46	2.97
B382146		5.10	0.122		<0.5	7.02	7160	1390	2.6	15	2.25	<0.5	7	48	38	2.56
B382147		4.00	0.018		<0.5	7.11	560	1560	3.2	3	2.29	<0.5	6	27	20	2.43
B382148		2.68	0.034		<0.5	7.82	1665	1620	3.2	6	2.31	<0.5	7	51	37	2.61
B382149		<0.02	0.034													
B382150		0.10	4.52		8.8	7.20	21	470	0.9	2	2.94	1.4	17	21	124	4.10
B382151		5.24	0.022		<0.5	7.71	906	1620	3.2	4	2.46	<0.5	6	30	23	2.55

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B382104		0.01	3.66	0.73	225	2	1.37	20	620	23	0.31	7	451	0.30	37	30
B382105		<0.01	3.73	0.78	227	5	1.46	19	650	18	0.36	<5	518	0.32	38	20
B382106		0.01	3.89	0.78	212	4	1.31	16	620	20	0.54	8	468	0.30	36	20
B382107		0.01	3.96	0.57	206	2	1.21	10	520	26	0.26	8	444	0.26	29	20
B382108		0.01	3.88	0.70	219	2	1.24	17	550	26	0.24	9	459	0.27	30	20
B382109																
B382110		<0.01	1.72	1.34	454	3	3.13	49	660	20	0.61	<5	204	0.31	91	<10
B382111		0.01	3.89	0.67	234	2	1.19	14	530	25	0.20	6	432	0.27	31	30
B382112		0.01	5.20	0.50	210	1	0.62	16	560	20	0.62	17	315	0.24	31	30
B382113		0.01	3.85	0.78	198	1	1.45	17	630	19	0.33	5	492	0.31	36	20
B382114		0.01	3.74	0.76	178	1	1.33	18	630	17	0.27	9	451	0.30	34	20
B382115		0.02	4.13	0.62	232	1	0.57	17	560	29	1.57	28	320	0.25	31	30
B382125		0.01	3.87	0.73	231	3	1.45	17	570	30	0.18	<5	450	0.29	36	20
B382126		0.01	3.90	0.77	232	2	1.40	20	630	24	0.28	<5	435	0.30	36	20
B382127		0.01	4.10	0.66	201	8	1.03	18	580	19	0.35	9	407	0.27	33	20
B382128		0.01	3.73	0.76	226	1	1.42	19	630	18	0.26	5	488	0.30	35	20
B382129																
B382130		0.03	3.61	1.11	498	3	3.38	12	1920	11	0.23	6	653	0.34	174	<10
B382131		0.01	4.00	0.59	209	4	0.92	16	580	25	0.48	18	355	0.28	32	30
B382132		0.05	3.14	0.98	538	3	0.28	18	530	152	1.75	83	222	0.23	29	30
B382133		0.01	4.17	0.66	241	1	0.95	21	660	16	0.42	15	370	0.31	39	20
B382134		0.01	4.01	0.51	267	3	0.76	20	580	15	0.30	12	343	0.28	34	20
B382135		0.01	4.12	0.47	243	5	0.57	16	600	15	0.23	11	304	0.30	35	30
B382136		<0.01	0.03	11.20	166	<1	0.01	2	540	2	0.02	<5	103	0.01	2	<10
B382137		0.01	4.06	0.58	197	6	0.51	16	610	25	0.28	20	316	0.28	32	30
B382138		0.02	3.83	0.53	249	2	0.44	20	610	64	0.89	23	238	0.28	34	30
B382139		0.01	3.84	0.77	199	1	1.15	20	570	17	0.28	9	425	0.28	35	20
B382145		0.02	4.32	0.79	234	18	0.75	17	550	28	0.90	18	342	0.26	34	40
B382146		0.01	3.63	0.66	190	9	1.08	20	570	17	0.50	11	399	0.26	33	30
B382147		0.01	3.64	0.72	215	2	1.68	20	630	20	0.26	<5	516	0.30	35	20
B382148		<0.01	3.84	0.83	200	2	1.69	20	690	24	0.36	<5	538	0.32	39	20
B382149																
B382150		0.01	2.25	1.32	970	13	1.69	13	930	24	0.70	<5	423	0.37	146	10
B382151		<0.01	3.65	0.83	234	2	1.73	22	690	19	0.28	5	531	0.32	38	10

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060237

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B382104		32
B382105		26
B382106		28
B382107		28
B382108		36
B382109		
B382110		212
B382111		37
B382112		18
B382113		23
B382114		20
B382115		32
B382125		44
B382126		35
B382127		22
B382128		26
B382129		
B382130		54
B382131		58
B382132		205
B382133		20
B382134		22
B382135		22
B382136		4
B382137		20
B382138		68
B382139		24
B382145		30
B382146		22
B382147		32
B382148		28
B382149		
B382150		95
B382151		32

Comments: Additional Au assay value for sample B381906 is 0.379 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05060235

Project: Dublin Gulch-1735

P.O. No.:

This report is for 114 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 21-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B381927		0.36	0.006	<0.5	6.08	155	540	1.2	<2	0.72	<0.5	8	43	14	2.35	0.01
B381928		3.70	0.038	0.5	7.92	2360	1330	3.5	5	2.38	<0.5	9	36	72	2.58	0.01
B381929		<0.02	0.036													
B381930		0.10	0.094	<0.5	7.18	112	600	2.7	<2	0.53	<0.5	61	1235	393	8.64	0.04
B381931		0.82	0.022	<0.5	7.94	548	1360	3.9	<2	2.35	<0.5	7	39	78	2.38	<0.01
B381932		2.34	0.042	0.8	7.32	1135	1250	3.2	2	2.55	<0.5	8	33	67	2.30	<0.01
B381933		0.40	0.012	<0.5	7.72	415	1440	3.6	<2	2.16	<0.5	8	39	74	2.43	<0.01
B381934		0.36	0.018	<0.5	7.49	395	1290	3.5	<2	2.20	<0.5	8	38	70	2.51	<0.01
B381935		3.38	0.037	0.8	7.26	1370	1380	3.6	<2	2.36	<0.5	10	41	77	2.62	<0.01
B381936		2.00	<0.005	<0.5	0.12	<5	20	<0.5	<2	20.00	<0.5	<1	2	2	0.21	<0.01
B381937		4.18	0.023	0.8	8.08	728	1460	3.6	<2	2.69	<0.5	8	34	72	2.62	0.01
B381938		5.24	0.021	<0.5	7.56	1465	1470	3.7	<2	2.08	<0.5	8	34	77	2.25	0.01
B381939		2.14	0.020	1.0	7.30	917	1100	2.9	<2	2.36	<0.5	7	33	84	2.41	0.01
B381940		2.92	0.027	0.5	7.53	1195	1430	3.8	3	1.77	<0.5	6	33	77	2.35	0.01
B381941		2.06	0.066	0.9	7.74	1315	1110	3.1	3	2.01	<0.5	8	36	85	2.46	0.02
B381942		1.92	0.071	0.9	7.52	1620	1100	3.1	3	1.88	<0.5	8	34	99	2.54	0.01
B381943		5.20	0.030	0.5	7.61	1200	1260	3.0	<2	1.97	<0.5	7	33	72	2.52	0.01
B381944		0.96	0.010	0.5	7.67	547	1270	2.9	<2	1.81	<0.5	6	35	96	2.56	0.01
B381945		3.76	0.071	0.6	7.62	2410	730	3.0	2	0.94	<0.5	8	33	130	5.61	0.03
B381946		2.38	0.115	1.0	7.12	2100	600	3.2	<2	1.15	1.5	6	32	152	4.98	0.04
B381947		1.36	0.017	<0.5	7.45	884	1020	2.9	2	2.81	<0.5	6	32	83	2.82	0.01
B381948		4.56	0.218	2.0	7.97	4170	1270	3.4	11	2.11	<0.5	13	34	85	3.28	0.02
B381961		2.60	0.025	<0.5	7.63	1020	1560	3.3	<2	2.16	<0.5	9	40	74	2.23	0.01
B381962		2.58	0.015	0.5	7.76	705	1470	3.3	<2	2.34	<0.5	8	40	70	2.37	<0.01
B381963		3.02	0.038	1.7	7.66	523	1230	2.9	<2	2.12	1.9	7	38	84	3.13	0.02
B381964		3.22	0.538	5.6	6.66	4270	240	2.4	<2	0.62	61.2	13	26	204	9.68	0.37
B381965		2.96	0.227	2.2	7.27	2130	630	2.9	7	0.91	2.7	10	31	127	5.70	0.03
B381966		2.58	0.104	1.7	6.43	1820	360	2.6	<2	2.65	38.3	8	22	164	6.39	0.19
B381967		2.86	0.474	8.2	6.69	6410	320	2.6	4	0.53	18.8	11	29	170	6.93	0.13
B381968		4.14	0.124	2.7	7.35	871	380	2.9	<2	1.52	24.8	6	28	266	5.61	0.14
B381969		<0.02	0.114													
B381970		0.10	4.53	9.8	8.12	<5	500	0.9	<2	2.93	0.6	20	20	124	4.37	0.02
B381971		6.18	0.183	4.9	7.08	578	730	2.8	<2	2.42	42.7	7	30	133	4.72	0.22
B381977		4.64	0.048	<0.5	7.66	1800	1790	2.8	<2	2.15	<0.5	12	33	102	3.10	0.01
B381978		6.54	0.065	0.7	7.51	699	1180	2.9	<2	2.02	<0.5	8	35	108	3.44	0.01
B381979		6.20	0.025	0.5	7.68	1340	1460	3.0	<2	1.60	<0.5	10	33	97	2.58	<0.01
B381980		5.30	0.137	<0.5	7.45	3470	1430	3.0	3	1.71	<0.5	10	34	108	2.69	<0.01
B381981		3.74	0.280	0.5	7.24	>10000	1320	3.0	32	1.44	<0.5	23	38	170	4.30	0.01
B381982		2.82	0.160	<0.5	7.44	6200	1380	3.0	22	1.18	<0.5	14	38	132	3.61	<0.01
B381983		5.50	0.175	<0.5	7.19	2550	1150	2.7	31	2.05	<0.5	8	30	214	4.34	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B381927		1.96	0.50	520	<1	1.17	17	160	10	0.05	<5	115	0.22	46	<10	26
B381928		3.91	0.89	190	1	1.70	12	610	19	0.41	7	528	0.28	41	<10	32
B381929																
B381930		2.26	0.61	387	9	0.13	496	340	157	0.02	12	51	0.24	92	30	619
B381931		4.51	0.71	173	1	1.78	11	590	11	0.19	<5	534	0.30	46	10	23
B381932		4.05	0.61	240	2	1.64	12	580	17	0.05	<5	438	0.27	42	20	31
B381933		4.35	0.71	174	2	1.78	13	610	14	0.09	<5	538	0.29	46	10	20
B381934		4.13	1.00	191	1	1.77	11	620	12	0.14	<5	533	0.29	47	10	22
B381935		3.93	0.84	198	1	1.78	13	580	13	0.31	<5	533	0.29	48	10	114
B381936		0.04	11.80	165	<1	0.02	1	560	4	0.02	<5	110	<0.01	1	10	7
B381937		3.66	0.89	201	1	1.56	14	610	12	0.22	<5	437	0.28	44	20	16
B381938		3.81	0.71	148	1	1.57	12	580	14	0.27	7	451	0.28	43	10	18
B381939		3.82	0.93	204	3	1.36	10	570	12	0.44	<5	405	0.26	40	20	148
B381940		3.98	0.66	165	1	1.38	13	570	14	0.25	<5	402	0.28	43	20	48
B381941		3.90	0.80	186	2	1.04	12	590	24	0.34	21	380	0.27	43	20	58
B381942		3.81	0.70	176	3	1.04	7	590	28	0.50	17	340	0.26	41	20	83
B381943		4.08	0.84	242	2	0.77	9	600	15	0.25	15	336	0.26	41	20	65
B381944		4.34	0.76	229	1	0.94	8	590	7	0.19	18	341	0.27	43	20	43
B381945		3.82	0.84	445	2	0.07	9	590	68	1.90	33	88	0.21	39	30	147
B381946		3.40	0.58	225	<1	0.06	11	570	128	2.22	38	130	0.20	37	30	296
B381947		3.92	1.10	299	1	0.79	8	570	22	0.24	14	441	0.26	41	30	49
B381948		4.08	0.79	333	2	0.91	14	580	230	0.75	37	312	0.26	42	30	214
B381961		4.41	0.83	207	1	1.15	13	620	19	0.38	12	367	0.29	47	20	33
B381962		4.33	0.91	222	1	1.15	11	630	9	0.33	11	381	0.29	47	20	33
B381963		3.99	0.90	444	1	0.34	13	610	287	0.72	134	236	0.28	44	10	518
B381964		3.03	0.67	1180	56	0.03	9	470	2550	6.52	1005	20	0.18	34	30	8780
B381965		3.41	0.80	1165	2	0.04	12	560	707	2.59	305	33	0.21	40	30	566
B381966		2.90	1.18	3230	1	0.02	11	480	1290	3.62	642	54	0.18	32	20	5990
B381967		3.22	0.77	868	1	0.03	10	520	4280	4.11	1505	20	0.17	37	30	2920
B381968		3.46	0.94	1680	2	0.03	10	560	671	3.40	313	40	0.21	40	20	3760
B381969																
B381970		2.32	1.42	1005	13	1.70	14	890	29	0.72	<5	424	0.38	153	<10	110
B381971		3.22	1.15	2830	1	0.03	13	510	3400	2.69	1455	52	0.21	37	30	6640
B381977		4.69	0.92	335	1	0.18	11	560	55	0.80	24	282	0.26	39	30	112
B381978		4.07	1.02	370	1	0.19	13	600	31	0.77	13	186	0.25	39	30	81
B381979		4.28	0.91	179	1	0.69	12	590	15	0.36	13	232	0.28	41	20	21
B381980		4.33	0.95	170	2	0.67	12	600	15	0.60	15	241	0.27	41	20	14
B381981		4.19	0.91	180	1	0.61	18	590	35	1.61	21	205	0.25	43	30	19
B381982		4.32	0.84	155	1	0.63	13	590	18	1.19	13	211	0.26	43	30	13
B381983		4.00	1.17	175	3	0.60	11	560	16	1.98	14	284	0.21	38	30	15

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B381984		2.62	0.045	<0.5	7.49	2920	1340	3.3	10	2.24	<0.5	8	30	114	2.61	0.01
B381985		2.72	0.027	<0.5	7.94	2070	1420	3.9	8	2.28	<0.5	9	34	122	2.28	<0.01
B381986		5.58	0.047	<0.5	8.00	3200	1480	3.7	11	2.11	<0.5	8	34	110	2.27	0.01
B381987		5.78	0.175	<0.5	7.88	4240	1380	3.5	32	1.82	<0.5	8	37	123	2.74	0.01
B381994		5.46	0.201	<0.5	7.68	7230	1360	3.2	30	2.04	<0.5	13	35	102	2.56	0.01
B381995		5.58	0.035	<0.5	7.99	1785	1380	3.5	9	2.19	<0.5	8	37	93	2.28	<0.01
B381996		2.30	<0.005	<0.5	0.12	22	20	<0.5	<2	19.75	<0.5	1	3	2	0.12	<0.01
B381997		5.76	0.070	<0.5	8.01	3420	1260	3.0	10	2.38	<0.5	8	33	98	2.48	0.01
B381998		3.04	0.683	3.1	6.45	>10000	170	2.8	45	1.73	3.8	17	26	519	5.20	0.07
B381999		2.38	0.023	<0.5	8.00	849	1310	3.6	9	2.42	<0.5	5	34	73	2.36	<0.01
B382000		6.28	0.062	<0.5	7.84	4030	1360	3.2	11	2.29	<0.5	8	34	71	2.55	0.01
B382001		0.54	0.151	0.6	7.93	3100	600	3.1	10	1.74	0.6	8	51	114	4.24	0.02
B382002		0.74	0.118	1.1	7.58	2410	600	3.0	31	1.68	0.5	6	28	127	3.95	0.01
B382003		4.74	0.131	<0.5	7.45	2980	1440	3.0	14	2.37	<0.5	8	31	124	2.61	0.01
B382004		6.00	0.076	<0.5	7.86	4710	1480	2.9	13	2.06	<0.5	9	30	100	2.40	<0.01
B382005		5.28	0.107	<0.5	7.62	6090	1440	2.9	19	2.14	<0.5	8	29	98	2.53	0.01
B382006		2.24	0.059	<0.5	7.54	3190	1490	3.0	10	2.17	<0.5	6	26	97	2.30	0.01
B382007		3.34	0.088	<0.5	7.42	3620	1510	2.6	12	2.17	<0.5	7	53	98	2.64	0.01
B382008		5.58	0.062	<0.5	7.70	2960	1550	3.0	7	2.17	<0.5	10	54	81	2.39	<0.01
B382009		<0.02	0.061													
B382010		0.10	2.82	<0.5	7.65	2120	740	13.2	<2	0.01	<0.5	<1	142	102	3.56	0.09
B382011		5.58	0.039	<0.5	7.76	1675	1340	3.0	7	2.42	<0.5	7	31	73	2.34	<0.01
B382012		6.04	0.048	<0.5	7.54	2600	1270	2.8	10	2.44	<0.5	7	28	80	2.35	0.01
B382018		4.30	0.027	<0.5	7.78	1325	1280	3.3	5	2.23	<0.5	7	56	55	2.18	<0.01
B382019		5.26	0.047	<0.5	8.01	3620	1450	3.1	8	2.25	<0.5	7	28	67	2.41	0.01
B382020		1.00	0.021	<0.5	7.84	920	1540	3.2	3	2.04	<0.5	9	26	47	2.36	<0.01
B382021		1.84	0.196	<0.5	8.06	5660	1560	2.3	131	2.20	<0.5	9	51	84	2.35	0.01
B382026		2.10	0.209	<0.5	6.92	>10000	1230	2.6	44	2.14	<0.5	7	25	50	2.38	0.02
B382027		2.50	0.083	<0.5	7.06	4910	1420	3.1	15	3.46	<0.5	7	26	57	2.36	<0.01
B382028		5.80	0.053	<0.5	8.07	4650	1580	3.4	12	2.05	<0.5	10	64	74	2.49	<0.01
B382029		<0.02	0.052													
B382030		0.10	2.73	<0.5	7.81	2100	730	13.6	<2	0.01	<0.5	1	149	101	3.50	0.08
B382031		2.54	0.090	<0.5	7.77	1600	1600	3.3	10	2.46	<0.5	8	30	54	2.40	<0.01
B382032		3.82	0.115	<0.5	7.51	6070	1270	2.7	7	2.38	<0.5	9	55	65	2.92	0.01
B382033		1.86	0.058	<0.5	7.93	4430	1540	3.3	7	2.04	<0.5	8	27	35	2.72	0.01
B382034		3.62	0.045	<0.5	7.54	2290	1540	2.7	6	2.50	<0.5	5	24	56	2.29	0.01
B382035		4.78	0.082	<0.5	7.74	6590	1540	2.8	7	2.18	<0.5	10	52	64	2.62	0.01
B382036		1.50	<0.005	<0.5	0.14	15	20	<0.5	<2	20.1	<0.5	<1	2	2	0.12	<0.01
B382037		2.60	0.496	2.2	5.35	>10000	130	2.1	51	3.02	<0.5	15	51	311	6.92	0.05
B382038		2.80	0.153	<0.5	6.98	3300	1270	2.9	56	1.88	<0.5	8	25	29	2.14	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B381984		4.35	1.15	170	2	0.74	10	550	12	0.78	13	351	0.24	39	20	14
B381985		4.25	0.63	131	1	1.51	12	610	13	0.60	<5	488	0.27	41	10	13
B381986		4.59	0.60	133	3	1.38	12	590	19	0.55	9	445	0.26	39	20	15
B381987		4.42	0.75	126	2	1.47	13	570	22	1.10	10	496	0.26	40	20	14
B381994		4.33	0.80	136	1	1.36	13	570	13	0.70	10	485	0.26	40	40	14
B381995		4.41	0.72	157	1	1.60	12	610	11	0.49	5	539	0.28	43	20	16
B381996		0.04	11.20	161	<1	0.01	3	450	3	0.01	<5	113	<0.01	2	<10	7
B381997		4.42	1.09	217	3	0.98	10	570	20	0.47	13	410	0.26	41	10	19
B381998		2.69	0.85	272	3	0.07	12	480	208	3.34	129	97	0.19	34	30	558
B381999		4.66	0.70	202	2	1.42	10	610	14	0.37	6	462	0.28	43	20	14
B382000		4.06	0.92	191	1	1.46	14	630	9	0.52	9	471	0.29	45	10	12
B382001		3.63	0.79	273	2	0.21	18	650	88	2.22	64	111	0.27	42	30	104
B382002		3.45	0.75	291	2	0.06	14	660	212	1.90	140	76	0.26	40	30	63
B382003		4.15	0.86	154	2	1.42	17	660	15	0.64	7	457	0.30	39	30	16
B382004		4.47	0.85	122	1	1.40	21	650	13	0.58	6	454	0.30	39	10	10
B382005		4.43	0.84	149	2	1.36	19	640	19	0.60	11	407	0.30	39	10	14
B382006		4.27	0.79	139	2	1.49	17	620	13	0.54	<5	448	0.30	38	10	11
B382007		4.70	0.87	160	1	1.17	18	620	21	0.70	11	386	0.28	38	20	21
B382008		4.39	0.80	130	1	1.69	21	640	11	0.54	<5	518	0.31	41	10	11
B382009																
B382010		3.29	0.39	70	2	0.09	10	340	27	0.02	156	148	0.25	107	10	12
B382011		4.17	0.89	163	1	1.47	16	610	11	0.47	<5	484	0.28	40	20	12
B382012		4.44	0.85	159	1	1.13	13	570	14	0.54	5	418	0.26	40	10	11
B382018		4.44	0.70	150	<1	1.88	15	590	12	0.45	<5	571	0.28	42	10	16
B382019		3.86	0.77	191	1	1.67	18	640	16	0.47	7	482	0.30	39	20	17
B382020		3.86	0.74	165	1	1.84	19	650	14	0.35	<5	554	0.32	39	20	18
B382021		5.68	0.78	160	8	1.18	14	620	16	0.58	17	479	0.28	35	50	11
B382026		3.65	0.64	129	1	1.18	15	540	15	0.68	12	393	0.25	32	20	10
B382027		4.11	0.80	182	1	1.48	14	580	14	0.48	5	560	0.27	35	20	15
B382028		4.58	0.81	125	1	1.66	18	660	15	0.61	8	586	0.31	40	30	9
B382029																
B382030		3.26	0.39	69	2	0.09	14	340	27	0.02	155	145	0.27	106	20	12
B382031		4.11	0.74	172	1	1.68	15	640	16	0.51	8	547	0.30	40	10	14
B382032		4.63	0.81	225	1	0.77	19	580	19	0.62	17	331	0.24	34	20	23
B382033		4.26	0.72	213	5	1.44	17	600	19	0.44	6	443	0.28	36	20	32
B382034		4.64	0.62	203	4	0.79	16	610	18	0.63	12	331	0.27	35	20	16
B382035		4.37	0.74	165	2	1.20	20	570	16	0.60	8	420	0.27	35	20	14
B382036		0.04	12.10	150	<1	0.02	4	490	<2	0.01	<5	114	0.01	3	<10	8
B382037		2.82	0.58	278	1	0.58	14	400	304	5.83	112	323	0.18	24	20	106
B382038		4.39	0.68	173	3	1.31	15	520	25	0.27	8	428	0.24	31	20	28

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B382039		4.16	0.082	<0.5	7.34	3780	1350	3.0	18	2.41	<0.5	9	61	50	2.38	0.01
B382040		2.20	0.024	<0.5	7.64	496	1530	3.5	<2	2.03	<0.5	7	31	31	2.33	0.01
B382041		2.16	0.035	<0.5	8.28	1205	1700	3.2	7	2.47	<0.5	8	50	32	2.57	0.01
B382042		1.70	0.027	<0.5	8.13	1555	1660	3.1	4	2.42	<0.5	7	23	40	2.50	0.01
B382043		4.88	0.022	<0.5	7.91	1755	1580	3.5	4	2.17	<0.5	7	46	31	2.37	0.01
B382044		6.96	0.072	<0.5	8.18	4300	1610	3.5	14	1.59	<0.5	9	26	83	2.55	0.01
B382045		4.78	0.058	<0.5	8.32	3860	1580	3.3	11	2.01	<0.5	9	49	67	2.35	<0.01
B382051		6.46	0.166	<0.5	7.68	9860	1530	3.3	35	2.33	<0.5	8	27	72	2.68	0.01
B382052		2.68	0.183	<0.5	8.05	6360	1780	3.3	33	2.40	<0.5	10	26	86	2.54	0.01
B382053		2.78	0.376	<0.5	7.77	>10000	1400	3.2	62	2.06	<0.5	11	55	89	3.55	0.01
B382054		3.88	0.240	<0.5	7.97	>10000	1660	2.7	33	1.45	<0.5	8	25	50	2.86	0.01
B382055		2.80	0.141	<0.5	8.13	6040	1720	3.1	67	2.38	<0.5	9	50	75	2.55	0.01
B382056		2.28	<0.005	<0.5	0.13	24	20	<0.5	<2	20.00	<0.5	<1	4	2	0.12	<0.01
B382057		2.36	0.139	<0.5	7.56	7460	1340	2.9	15	3.15	<0.5	10	24	68	2.90	0.01
B382058		1.60	0.241	<0.5	7.45	>10000	1440	2.4	22	3.09	<0.5	13	44	73	2.65	0.01
B382059		2.68	0.114	<0.5	8.23	>10000	1560	3.3	30	1.92	<0.5	8	26	86	3.13	0.01
B382060		4.06	0.181	<0.5	7.53	7990	1420	3.4	25	2.07	<0.5	8	51	76	2.42	0.01
B382061		1.12	0.027	<0.5	8.09	3800	1290	4.5	5	2.14	<0.5	5	21	81	1.74	0.01
B382062		1.26	0.019	<0.5	7.73	3320	1280	4.6	4	2.01	<0.5	5	38	87	1.70	0.01
B382080		2.10	0.026	<0.5	7.47	3190	1420	4.4	45	2.36	<0.5	5	22	63	1.70	0.01
B382081		1.16	0.198	<0.5	7.96	7640	1300	4.8	25	2.47	<0.5	5	24	46	2.11	0.01
B382082		1.58	0.072	<0.5	7.97	3830	1280	4.8	7	2.12	<0.5	5	22	58	1.76	0.01
B382083		2.66	0.098	<0.5	7.79	6170	1360	4.2	21	1.98	<0.5	7	25	81	2.06	0.01
B382084		1.80	0.014	<0.5	7.78	693	1460	3.0	3	1.96	<0.5	5	23	94	2.10	0.01
B382089		<0.02	0.012													
B382090		0.10	4.39	8.1	8.05	18	500	0.9	<2	2.82	1.4	20	20	130	4.40	0.02
B382091		3.96	0.206	0.5	7.90	8500	1700	2.8	23	2.21	<0.5	10	25	52	2.85	0.01
B382092		6.12	0.060	<0.5	8.08	2770	1640	3.2	10	2.42	<0.5	8	30	43	2.76	<0.01
B382093		5.04	0.046	<0.5	7.60	1625	1030	3.2	6	2.89	<0.5	8	25	42	2.40	0.01
B382094		3.10	0.034	<0.5	8.87	755	1760	3.3	4	2.32	<0.5	8	27	34	2.73	0.01
B382095		3.54	0.030	<0.5	7.99	2130	1600	3.0	5	2.65	<0.5	9	24	37	2.49	<0.01
B382096		1.46	<0.005	<0.5	0.13	10	20	<0.5	<2	18.95	<0.5	1	2	2	0.18	<0.01
B382097		3.28	0.054	<0.5	7.59	2750	1520	2.9	8	2.23	<0.5	7	23	34	2.39	0.01
B382098		2.14	0.121	<0.5	8.08	4190	1620	3.0	20	2.61	<0.5	8	26	36	2.63	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060235

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B382039		4.01	0.66	245	1	1.16	16	620	36	0.37	9	409	0.29	37	20	61
B382040		4.02	0.74	220	1	1.64	19	620	29	0.20	<5	515	0.30	38	10	42
B382041		4.16	0.91	251	1	1.52	20	650	32	0.23	<5	558	0.32	39	10	42
B382042		4.18	0.90	236	<1	1.38	20	630	26	0.25	<5	538	0.32	38	20	34
B382043		4.34	0.80	233	<1	1.39	20	590	26	0.25	5	508	0.30	37	10	42
B382044		4.47	0.86	130	1	1.39	17	600	16	0.51	5	514	0.30	37	20	13
B382045		4.65	0.79	150	1	1.41	18	600	15	0.41	<5	513	0.29	37	10	16
B382051		4.34	0.86	135	1	1.46	18	590	12	0.71	7	526	0.28	34	20	12
B382052		4.61	0.74	148	<1	1.40	19	640	30	0.55	11	527	0.31	37	10	18
B382053		4.53	0.63	128	1	1.46	19	590	17	1.28	18	493	0.29	36	20	13
B382054		5.25	0.58	140	1	0.98	16	590	51	0.83	26	396	0.28	32	120	25
B382055		4.60	0.73	162	1	1.56	21	650	19	0.58	12	522	0.31	38	20	16
B382056		0.03	12.15	156	<1	0.01	5	520	<2	0.01	<5	114	<0.01	2	<10	8
B382057		4.23	0.78	251	1	1.06	18	610	33	0.70	21	406	0.28	34	20	27
B382058		5.01	0.69	210	1	0.79	18	590	36	0.88	24	368	0.26	33	30	19
B382059		3.88	0.76	135	2	1.44	20	620	15	0.84	8	484	0.31	37	20	15
B382060		4.13	0.65	128	1	1.36	17	550	13	0.65	11	426	0.26	36	30	17
B382061		4.22	0.53	82	<1	1.65	10	450	20	0.55	<5	401	0.16	37	30	16
B382062		4.28	0.54	77	<1	1.68	10	450	17	0.52	6	405	0.16	37	20	14
B382080		3.72	0.66	120	<1	1.80	9	450	49	0.53	7	371	0.15	36	10	22
B382081		3.60	0.59	132	1	1.96	11	460	33	0.65	6	420	0.16	37	10	26
B382082		3.58	0.58	114	<1	1.90	10	460	16	0.52	<5	405	0.16	38	10	23
B382083		4.31	0.85	122	2	1.50	13	460	12	0.53	7	416	0.18	36	10	25
B382084		3.94	0.88	153	2	1.19	21	610	17	0.36	<5	485	0.30	34	20	22
B382089																
B382090		2.36	1.39	1015	13	1.72	15	920	22	0.71	<5	432	0.38	156	<10	100
B382091		4.49	0.76	174	1	1.32	25	670	25	0.67	8	482	0.29	36	20	18
B382092		3.93	0.83	214	<1	1.74	21	660	14	0.38	<5	559	0.34	39	10	22
B382093		4.23	0.56	208	3	0.66	20	640	18	0.36	13	307	0.31	38	30	25
B382094		4.11	0.87	235	9	1.56	23	680	21	0.32	<5	533	0.34	40	40	30
B382095		4.12	0.84	227	<1	1.26	22	640	15	0.35	<5	494	0.32	38	20	25
B382096		0.04	11.60	166	<1	0.01	4	580	<2	0.01	<5	110	0.01	2	<10	8
B382097		3.89	0.82	215	6	1.16	20	600	14	0.32	<5	470	0.31	36	20	25
B382098		4.07	0.83	221	<1	1.44	22	660	16	0.40	<5	525	0.33	39	20	24

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05060561

Project: Dublin Gulch-1735

P.O. No.:

This report is for 181 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 22-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380611		0.64	0.006	1.1	4.18	120	560	1.0	<2	0.31	<0.5	11	119	40	3.42	0.02
B380612		3.02	0.041	<0.5	1.19	122	40	<0.5	<2	0.03	<0.5	3	15	26	1.29	0.03
B380613		2.68	0.137	<0.5	1.65	1355	70	<0.5	2	0.07	<0.5	6	28	47	1.96	0.06
B380614		5.26	0.025	<0.5	1.53	299	70	<0.5	<2	0.05	<0.5	2	43	17	1.10	0.02
B380615		2.98	0.113	<0.5	1.74	164	40	<0.5	<2	0.03	<0.5	3	20	29	1.52	0.19
B380616		2.10	<0.005	<0.5	0.11	<5	10	<0.5	<2	19.05	<0.5	<1	3	3	0.12	<0.01
B380617		5.76	0.025	<0.5	1.82	122	70	<0.5	<2	0.05	<0.5	4	26	28	1.44	0.11
B380618		Not Recvd														
B380619		3.36	0.011	<0.5	1.57	126	80	<0.5	<2	0.03	<0.5	4	44	14	1.37	0.02
B380620		5.90	0.084	<0.5	2.28	119	120	<0.5	<2	0.04	<0.5	5	27	43	2.52	0.14
B380621		1.18	0.012	<0.5	1.67	142	90	<0.5	<2	0.03	<0.5	4	50	19	2.24	0.03
B380622		1.04	0.012	<0.5	1.82	176	100	<0.5	<2	0.04	<0.5	6	20	30	2.58	0.03
B380623		1.26	0.009	<0.5	7.16	40	360	1.0	<2	0.05	<0.5	19	108	43	4.14	0.57
B380624		2.16	<0.005	<0.5	5.00	22	280	0.7	<2	0.04	<0.5	12	39	23	2.75	0.19
B380625		3.74	<0.005	<0.5	5.49	19	270	0.7	<2	0.06	<0.5	10	49	21	3.71	0.09
B380626		5.42	<0.005	<0.5	5.37	41	250	0.8	<2	0.06	<0.5	14	34	20	3.12	0.11
B380627		3.36	<0.005	<0.5	7.38	34	480	1.1	<2	0.06	<0.5	12	60	24	3.29	0.08
B380628		6.34	<0.005	<0.5	9.06	36	660	1.4	<2	0.11	<0.5	20	64	33	4.87	0.06
B380629		0.04	<0.005													
B380630		0.10	0.088	<0.5	6.96	104	570	2.5	<2	0.52	<0.5	58	1125	379	8.55	0.03
B380631		5.64	0.007	<0.5	7.43	92	530	1.6	<2	0.11	<0.5	14	68	23	3.73	0.01
B380632		5.28	<0.005	<0.5	6.84	246	440	1.4	<2	0.10	<0.5	14	46	26	3.31	0.01
B380633		4.56	<0.005	<0.5	6.50	24	390	1.8	<2	0.33	<0.5	13	57	23	3.94	<0.01
B380634		6.14	0.005	<0.5	9.18	34	840	2.7	<2	0.38	<0.5	17	73	39	3.77	0.01
B380635		5.76	<0.005	<0.5	7.52	10	560	2.0	<2	0.27	<0.5	13	71	25	3.58	<0.01
B380636		2.54	<0.005	<0.5	0.12	<5	10	<0.5	<2	19.20	<0.5	<1	2	2	0.11	<0.01
B380637		6.16	<0.005	<0.5	8.07	6	620	2.1	<2	0.38	<0.5	15	61	32	3.81	<0.01
B380638		5.70	<0.005	<0.5	7.49	9	540	1.7	<2	0.60	<0.5	12	53	23	3.55	<0.01
B380639		5.68	<0.005	<0.5	7.51	8	550	1.9	<2	0.34	<0.5	13	54	27	3.65	<0.01
B380640		5.80	<0.005	<0.5	7.30	8	510	2.3	<2	0.28	<0.5	12	50	22	3.66	<0.01
B380641		1.06	0.008	<0.5	2.20	454	60	0.6	<2	0.32	<0.5	5	86	8	1.51	<0.01
B380642		1.20	0.006	<0.5	2.26	427	50	0.6	<2	0.32	<0.5	4	18	8	1.58	<0.01
B380643		3.96	<0.005	<0.5	8.46	45	680	1.9	<2	0.44	<0.5	15	93	33	3.96	<0.01
B380644		5.80	0.005	<0.5	8.47	11	700	2.0	<2	0.38	<0.5	15	66	43	4.40	0.02
B380645		4.58	<0.005	<0.5	6.56	<5	460	1.5	<2	0.27	<0.5	11	85	31	3.45	0.01
B380646		5.12	<0.005	<0.5	7.97	43	590	1.9	<2	0.36	<0.5	14	57	43	3.58	0.01
B380647		5.42	<0.005	<0.5	8.24	52	630	1.9	<2	0.32	<0.5	14	89	28	3.88	0.01
B380648		2.96	0.007	<0.5	4.20	<5	190	1.2	<2	1.28	<0.5	8	28	17	2.81	0.02
B380649		0.14	<0.005													
B380650		0.10	0.431	2.9	9.48	6	1060	1.2	2	1.48	<0.5	9	8	7190	3.23	0.04

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380611		1.30	0.64	332	2	0.29	29	240	13	0.18	<5	64	0.24	50	30	57
B380612		0.22	0.04	204	<1	0.02	6	60	3	0.32	<5	32	0.05	10	<10	19
B380613		0.35	0.05	252	1	0.01	15	190	3	0.69	<5	106	0.14	19	<10	14
B380614		0.46	0.06	126	<1	0.01	9	80	5	0.29	<5	35	0.07	14	<10	10
B380615		0.22	0.04	192	<1	0.01	11	120	2	0.44	7	62	0.08	16	<10	14
B380616		0.03	11.15	152	<1	0.01	3	530	<2	0.01	<5	106	0.01	3	<10	7
B380617		0.40	0.07	197	1	0.01	13	160	3	0.46	7	75	0.11	19	<10	15
B380618																
B380619		0.52	0.07	212	1	0.01	8	90	4	0.21	7	41	0.08	16	<10	19
B380620		0.60	0.10	395	<1	0.01	16	150	7	0.63	8	71	0.11	25	<10	31
B380621		0.42	0.07	452	1	0.01	8	250	5	0.20	<5	130	0.06	17	<10	33
B380622		0.43	0.08	548	1	0.01	11	330	5	0.23	6	174	0.06	20	<10	41
B380623		1.60	0.26	684	2	0.03	55	330	4	1.15	12	128	0.35	126	10	98
B380624		1.04	0.16	474	1	0.03	26	250	5	0.62	8	110	0.23	55	<10	72
B380625		0.86	0.19	583	1	0.05	23	300	13	0.20	<5	61	0.24	43	<10	94
B380626		0.89	0.18	557	1	0.06	23	280	14	0.08	<5	86	0.25	45	<10	101
B380627		1.76	0.29	508	1	0.10	29	190	25	0.07	<5	55	0.32	69	<10	101
B380628		2.40	0.49	645	1	0.15	45	290	20	0.34	<5	65	0.39	91	<10	132
B380629																
B380630		2.21	0.57	376	9	0.13	463	340	147	0.02	14	49	0.23	89	30	601
B380631		2.09	0.37	477	1	0.12	35	360	17	0.35	<5	49	0.31	71	<10	106
B380632		1.78	0.37	449	1	0.11	31	280	19	0.30	<5	39	0.29	63	<10	103
B380633		1.70	0.82	466	1	0.53	33	300	16	0.31	<5	48	0.29	57	<10	99
B380634		3.65	0.99	302	1	0.35	39	380	23	0.60	<5	67	0.41	104	<10	73
B380635		2.61	1.01	291	1	0.57	32	300	16	0.29	<5	53	0.33	74	<10	78
B380636		0.03	11.20	147	<1	0.01	5	500	3	0.01	26	104	<0.01	2	<10	7
B380637		2.74	1.01	286	1	0.68	37	370	27	0.31	183	62	0.38	77	<10	84
B380638		2.42	1.00	326	1	0.69	28	330	15	0.23	7	70	0.35	69	<10	73
B380639		2.54	1.04	298	1	0.56	33	330	14	0.32	35	66	0.34	71	<10	75
B380640		2.26	0.98	280	1	0.54	29	290	13	0.39	<5	44	0.31	70	<10	73
B380641		0.26	0.42	177	1	0.41	6	140	7	0.14	225	22	0.11	16	<10	19
B380642		0.25	0.47	180	<1	0.49	7	150	8	0.14	<5	22	0.11	15	<10	23
B380643		3.23	1.26	284	<1	0.25	35	330	11	0.48	58	50	0.36	86	10	76
B380644		3.05	1.24	419	<1	0.26	40	350	12	1.16	<5	53	0.33	92	<10	72
B380645		2.09	0.96	420	<1	0.20	28	290	9	0.53	6	45	0.25	65	<10	63
B380646		2.67	1.02	309	<1	0.30	34	300	9	0.70	16	71	0.30	78	<10	49
B380647		2.77	1.08	456	1	0.25	33	330	14	0.37	<5	52	0.34	79	<10	77
B380648		0.87	0.84	734	1	0.29	18	170	6	0.42	8	115	0.18	35	<10	58
B380649																
B380650		3.71	1.19	478	3	3.38	8	1940	6	0.23	<5	694	0.34	174	<10	57

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380651		5.60	<0.005	<0.5	7.37	<5	530	2.1	<2	0.28	<0.5	14	55	30	3.82	0.01
B380652		4.30	<0.005	<0.5	9.31	12	810	2.4	<2	0.24	<0.5	21	75	41	4.16	<0.01
B380653		2.24	<0.005	<0.5	10.35	<5	910	2.8	<2	0.19	<0.5	22	81	48	4.53	<0.01
B380654		1.54	<0.005	<0.5	8.72	11	660	2.4	<2	0.19	<0.5	20	67	37	4.70	0.01
B380655		4.50	<0.005	<0.5	6.27	<5	450	1.5	<2	0.36	<0.5	9	44	22	2.85	<0.01
B380656		1.84	<0.005	<0.5	0.14	<5	10	<0.5	<2	19.45	<0.5	<1	2	2	0.14	<0.01
B380657		2.68	<0.005	<0.5	3.61	<5	150	0.5	<2	0.63	<0.5	5	30	11	2.37	<0.01
B380658		3.06	<0.005	<0.5	9.25	31	760	2.6	<2	0.29	<0.5	18	70	44	4.30	<0.01
B380659		5.60	0.010	<0.5	6.94	43	490	1.8	<2	0.30	<0.5	15	51	37	3.97	<0.01
B380660		6.44	<0.005	<0.5	7.66	9	580	2.0	<2	0.38	<0.5	14	53	34	3.93	<0.01
B380661		2.10	<0.005	<0.5	7.27	8	540	1.9	<2	0.45	<0.5	13	132	32	3.95	<0.01
B380662		2.28	<0.005	<0.5	7.34	5	560	1.9	<2	0.42	<0.5	12	171	29	3.80	0.01
B380663		3.64	<0.005	<0.5	7.36	10	530	1.7	<2	0.21	<0.5	14	114	31	4.25	0.01
B380664		2.54	<0.005	<0.5	6.57	<5	420	1.3	<2	0.75	<0.5	11	170	24	3.71	0.01
B380665		5.14	<0.005	<0.5	6.32	16	440	1.5	<2	0.52	<0.5	11	128	26	3.02	0.01
B380666		4.90	<0.005	<0.5	9.09	18	780	2.3	<2	0.12	<0.5	22	192	39	4.46	0.01
B380667		0.58	0.015	<0.5	2.93	105	110	0.7	<2	0.06	<0.5	9	153	20	2.55	0.01
B380668		5.94	<0.005	<0.5	7.55	17	570	1.9	<2	0.23	<0.5	15	185	33	3.80	0.01
B380669		0.04	<0.005													
B380670		0.10	1.505	<0.5	6.71	1140	640	5.6	<2	0.01	<0.5	5	194	35	3.53	0.05
B380671		5.40	<0.005	<0.5	6.60	22	420	1.6	<2	0.39	<0.5	13	136	26	3.61	<0.01
B380672		4.20	<0.005	<0.5	7.48	<5	550	1.9	<2	0.39	<0.5	14	148	25	3.38	0.01
B380673		3.10	<0.005	<0.5	7.47	5	520	1.8	<2	0.24	<0.5	16	140	33	3.65	0.01
B380674		1.70	<0.005	<0.5	5.33	<5	220	1.0	<2	0.84	<0.5	8	167	21	2.51	0.01
B380675		5.10	<0.005	<0.5	6.68	<5	440	1.7	<2	0.31	<0.5	13	138	24	3.23	0.01
B380676		2.18	<0.005	<0.5	0.17	<5	20	<0.5	<2	20.2	<0.5	1	14	1	0.15	<0.01
B380677		4.12	<0.005	<0.5	5.67	9	300	1.4	<2	0.54	<0.5	10	128	18	3.27	0.01
B380678		4.28	<0.005	<0.5	6.34	11	360	1.9	<2	0.21	<0.5	12	166	22	3.78	0.01
B380679		1.10	0.280	1.5	1.03	>10000	30	0.5	5	0.04	1.1	44	225	15	6.77	0.05
B380680		1.60	0.014	<0.5	3.50	4080	150	1.0	<2	0.07	<0.5	10	174	42	3.77	0.02
B380681		0.78	<0.005	0.6	9.70	102	750	1.8	<2	0.15	<0.5	17	154	73	4.00	0.01
B380682		0.80	<0.005	<0.5	8.15	193	610	1.6	<2	0.13	<0.5	11	180	62	3.53	0.01
B380683		4.94	0.005	<0.5	4.33	1385	160	0.8	<2	0.81	<0.5	7	191	25	2.58	0.01
B380684		3.12	<0.005	<0.5	5.80	86	330	1.3	<2	0.40	<0.5	12	168	23	2.81	<0.01
B380685		4.28	<0.005	<0.5	7.89	19	530	2.0	<2	0.31	<0.5	20	167	32	4.41	0.01
B380686		3.92	<0.005	<0.5	5.70	119	360	1.3	<2	0.09	0.5	11	182	31	2.00	0.03
B380687		2.00	<0.005	<0.5	6.74	13	450	1.5	<2	0.36	<0.5	12	157	22	3.24	0.01
B380688		1.64	<0.005	0.5	10.80	59	910	2.5	<2	0.20	<0.5	25	162	64	5.15	0.01
B380689		0.04	<0.005													
B380690		0.10	3.29	1.3	7.73	<5	2250	3.4	<2	5.19	<0.5	28	156	104	5.54	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B380651		2.17	0.90	360	<1	0.56	32	260	13	0.63	<5	68	0.33	75	<10	81
B380652		3.30	0.98	356	1	0.49	48	360	23	0.85	5	82	0.35	108	<10	87
B380653		3.85	1.02	429	1	0.37	48	340	14	0.96	<5	86	0.43	120	<10	89
B380654		2.71	0.91	818	<1	0.28	45	320	16	0.65	7	50	0.36	94	<10	148
B380655		1.70	0.67	303	<1	0.82	19	260	11	0.42	<5	76	0.28	62	<10	59
B380656		0.03	11.65	138	<1	0.01	1	510	<2	0.01	<5	107	<0.01	2	<10	7
B380657		0.48	0.60	466	<1	1.23	10	180	8	0.24	<5	69	0.18	29	<10	38
B380658		3.02	1.02	273	1	0.51	41	330	17	0.68	<5	102	0.41	100	<10	85
B380659		2.02	1.00	367	<1	0.44	31	280	13	0.50	6	71	0.30	70	<10	89
B380660		2.31	0.99	316	<1	0.61	30	290	15	0.64	<5	91	0.33	75	<10	70
B380661		2.22	1.08	326	<1	0.65	32	280	11	0.63	<5	92	0.33	73	<10	77
B380662		2.25	1.02	320	1	0.64	29	280	15	0.58	<5	90	0.34	76	<10	74
B380663		2.36	1.14	305	<1	0.52	34	270	9	0.48	<5	56	0.30	76	<10	86
B380664		1.62	0.93	456	<1	0.79	24	300	14	0.47	<5	100	0.26	61	<10	71
B380665		1.68	0.78	373	2	1.00	24	240	8	0.45	<5	112	0.27	61	<10	55
B380666		3.39	0.99	572	1	0.27	50	400	29	0.65	<5	64	0.35	102	<10	156
B380667		0.65	0.51	323	1	0.19	26	140	8	0.32	<5	13	0.12	25	<10	95
B380668		2.30	0.95	283	1	0.64	34	280	19	0.41	<5	77	0.32	77	<10	80
B380669																
B380670		2.53	0.34	84	2	0.10	18	280	25	0.02	112	84	0.23	85	10	42
B380671		1.72	0.93	315	<1	0.85	31	260	16	0.43	<5	81	0.29	62	<10	77
B380672		2.28	0.87	413	<1	0.74	33	290	18	0.40	<5	73	0.33	73	<10	93
B380673		2.18	0.94	434	1	0.78	40	280	13	0.55	<5	57	0.32	77	<10	92
B380674		1.25	0.71	380	<1	1.18	23	210	8	0.40	<5	78	0.19	40	<10	51
B380675		1.88	0.85	343	1	0.76	30	300	15	0.30	<5	57	0.29	64	<10	76
B380676		0.04	11.95	170	<1	0.02	1	520	<2	0.01	<5	114	<0.01	1	<10	8
B380677		1.24	0.87	490	1	0.70	26	230	14	0.39	<5	59	0.24	49	<10	64
B380678		1.58	0.80	467	<1	0.21	32	230	16	0.41	<5	25	0.28	58	<10	88
B380679		0.13	0.18	57	1	0.06	33	30	146	4.81	98	8	0.03	12	<10	135
B380680		0.94	0.28	407	1	0.03	25	150	36	1.96	57	12	0.15	29	<10	114
B380681		3.51	0.63	562	<1	0.10	43	350	18	0.80	6	36	0.44	102	<10	51
B380682		3.03	0.52	493	1	0.08	34	300	21	0.76	<5	29	0.33	84	<10	51
B380683		0.76	0.54	529	1	1.00	21	210	40	0.26	<5	85	0.20	28	<10	81
B380684		1.43	0.70	475	1	1.10	31	240	14	0.34	<5	80	0.27	50	<10	80
B380685		2.17	0.92	541	1	0.76	44	280	26	0.55	6	67	0.36	79	<10	150
B380686		1.64	0.28	374	1	0.09	28	240	79	0.40	7	22	0.25	52	<10	222
B380687		1.80	0.75	405	<1	0.82	30	260	19	0.36	<5	61	0.29	66	<10	62
B380688		4.06	1.02	806	<1	0.33	60	360	22	0.58	<5	60	0.50	128	<10	144
B380689																
B380690		3.74	3.26	1135	15	2.53	69	2540	28	0.33	6	1795	0.44	183	<10	104

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380691		4.34	<0.005	<0.5	9.65	17	860	2.8	<2	0.24	<0.5	20	149	52	3.95	0.01
B380692		5.34	0.012	<0.5	9.69	57	850	2.8	<2	0.17	<0.5	21	153	56	3.94	0.01
B380693		4.78	<0.005	<0.5	9.07	11	710	2.7	<2	0.20	<0.5	21	134	42	4.66	0.01
B380694		4.46	<0.005	<0.5	9.12	14	690	2.4	<2	0.20	<0.5	22	164	41	4.68	0.01
B380695		0.84	<0.005	<0.5	6.33	<5	360	1.6	<2	0.17	<0.5	18	143	24	3.68	0.01
B380696		1.90	<0.005	<0.5	0.12	<5	10	<0.5	<2	19.10	<0.5	1	9	2	0.11	0.01
B380697		2.46	0.008	<0.5	5.76	79	340	1.5	<2	0.17	<0.5	14	125	28	3.42	0.02
B380698		4.90	<0.005	<0.5	6.59	9	460	1.6	<2	0.72	0.5	13	157	26	3.51	0.01
B380699		5.70	<0.005	<0.5	6.04	28	350	1.3	<2	0.65	<0.5	14	140	28	2.80	0.01
B380700		1.66	0.010	<0.5	3.49	176	90	0.7	<2	0.57	<0.5	8	191	12	1.93	0.01
B380701		1.50	<0.005	<0.5	7.28	103	590	1.9	<2	0.16	<0.5	19	158	30	3.75	<0.01
B380702		1.22	<0.005	<0.5	7.93	18	660	2.1	<2	0.16	<0.5	24	205	35	4.13	0.01
B380703		4.98	<0.005	<0.5	8.93	8	790	2.5	<2	0.24	<0.5	21	142	41	4.92	0.01
B380704		5.20	0.005	<0.5	7.58	34	570	2.0	<2	0.62	<0.5	18	183	37	3.98	0.01
B380705		1.92	<0.005	<0.5	4.78	15	270	0.9	<2	0.79	<0.5	9	155	23	2.23	<0.01
B380706		0.60	<0.005	<0.5	2.17	32	180	0.7	<2	0.56	<0.5	5	254	20	1.53	0.01
B380707		2.30	<0.005	<0.5	5.84	9	400	1.4	<2	0.52	<0.5	12	156	25	2.96	<0.01
B380708		5.56	<0.005	<0.5	6.13	13	420	1.5	<2	0.70	<0.5	11	180	23	2.84	<0.01
B380709		0.04	<0.005													
B380710		0.10	1.475	<0.5	6.52	1210	650	5.6	<2	0.01	<0.5	7	205	39	3.56	0.05
B380711		3.90	<0.005	<0.5	6.48	25	410	1.7	<2	0.65	<0.5	13	132	21	3.37	<0.01
B380712		2.26	0.021	<0.5	3.52	278	170	1.0	<2	0.52	<0.5	10	142	18	2.11	<0.01
B380713		2.86	0.007	<0.5	9.01	54	760	2.7	<2	0.39	<0.5	19	127	46	4.27	<0.01
B380714		5.80	<0.005	<0.5	4.09	5	220	0.8	<2	0.33	<0.5	7	115	10	1.73	<0.01
B380715		5.58	<0.005	<0.5	6.20	15	470	1.7	<2	0.69	<0.5	12	200	23	2.60	0.01
B380716		2.16	<0.005	<0.5	0.13	<5	10	<0.5	<2	19.40	<0.5	<1	8	2	0.11	<0.01
B380717		4.40	<0.005	<0.5	5.26	7	340	1.4	<2	0.53	<0.5	12	213	25	2.92	<0.01
B380718		4.84	<0.005	<0.5	7.91	17	630	2.0	<2	0.52	<0.5	14	160	32	3.91	<0.01
B380719		5.16	<0.005	<0.5	5.89	62	420	1.2	<2	0.49	<0.5	11	230	25	2.65	0.01
B380720		3.38	<0.005	<0.5	5.60	<5	270	1.4	<2	0.88	<0.5	9	134	22	3.27	0.01
B380721		0.98	<0.005	<0.5	8.65	<5	720	2.5	<2	0.86	<0.5	19	148	40	4.20	0.01
B380722		1.20	<0.005	<0.5	10.00	14	760	2.7	<2	0.86	<0.5	22	144	45	4.71	0.01
B380723		5.24	<0.005	<0.5	8.28	<5	650	2.1	<2	0.69	<0.5	17	192	48	3.95	<0.01
B380724		4.52	<0.005	<0.5	7.95	<5	630	2.0	<2	0.42	<0.5	16	151	42	4.83	<0.01
B380725		6.48	<0.005	<0.5	10.60	<5	870	2.8	<2	0.28	<0.5	17	150	35	4.75	0.01
B380726		4.74	<0.005	<0.5	9.11	11	680	2.4	<2	0.48	<0.5	15	121	43	4.49	0.01
B380727		4.88	<0.005	<0.5	8.25	10	680	2.3	<2	0.23	<0.5	16	160	34	3.88	0.01
B380728		5.96	<0.005	<0.5	6.23	<5	440	1.4	<2	0.63	<0.5	10	196	28	3.09	0.01
B380729		0.04	0.005													
B380730		0.10	0.092	<0.5	7.25	112	600	2.7	<2	0.54	<0.5	61	1265	406	8.86	0.03

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380691		3.61	0.94	354	<1	0.52	45	350	14	0.75	6	79	0.43	115	<10	84
B380692		3.70	0.96	326	5	0.36	49	330	16	0.89	<5	65	0.39	108	<10	81
B380693		3.03	1.02	367	<1	0.26	44	300	21	0.54	5	55	0.41	101	<10	110
B380694		2.67	0.85	561	<1	0.21	54	320	19	0.49	7	51	0.41	101	<10	160
B380695		1.34	0.58	770	<1	0.09	43	230	12	0.33	5	29	0.31	57	<10	143
B380696		0.03	11.25	153	<1	0.01	2	550	<2	0.01	<5	105	<0.01	1	<10	7
B380697		1.58	0.53	668	1	0.09	35	230	22	0.42	8	21	0.26	57	<10	167
B380698		2.25	0.93	642	<1	0.46	35	240	40	0.25	6	56	0.25	65	<10	135
B380699		1.64	0.73	457	1	0.80	31	220	14	0.31	<5	62	0.28	53	<10	70
B380700		0.50	0.48	395	1	0.91	14	170	10	0.18	<5	66	0.17	25	<10	42
B380701		2.37	0.76	598	<1	0.36	48	320	12	0.43	6	46	0.33	80	<10	140
B380702		2.62	0.80	650	<1	0.37	55	300	16	0.53	<5	46	0.37	92	<10	186
B380703		3.02	1.01	432	<1	0.17	46	300	15	0.84	<5	57	0.41	104	<10	113
B380704		2.36	1.01	420	1	0.27	39	320	20	0.65	<5	52	0.35	84	<10	87
B380705		0.96	0.51	305	<1	1.22	21	210	9	0.33	<5	96	0.23	38	<10	44
B380706		0.71	0.33	187	1	0.13	13	100	3	0.33	<5	37	0.13	23	<10	19
B380707		1.50	0.78	252	<1	0.70	30	310	9	0.31	<5	52	0.30	55	<10	59
B380708		1.65	0.77	280	1	0.69	27	260	12	0.30	<5	58	0.28	56	<10	51
B380709																
B380710		2.64	0.32	85	1	0.10	20	310	26	0.01	108	85	0.22	89	10	47
B380711		1.55	0.75	507	<1	0.23	33	280	17	0.26	5	38	0.30	61	<10	80
B380712		0.84	0.44	456	<1	0.04	18	160	<2	0.19	<5	21	0.17	30	<10	39
B380713		3.23	0.87	246	<1	0.20	45	340	19	0.91	<5	49	0.44	111	<10	102
B380714		0.84	0.40	185	<1	1.03	18	180	10	0.14	<5	49	0.19	30	<10	31
B380715		1.88	0.69	287	1	0.57	28	250	23	0.36	<5	60	0.28	61	<10	53
B380716		0.03	11.25	158	<1	0.01	3	550	<2	0.01	<5	112	<0.01	1	<10	7
B380717		1.30	0.62	422	2	0.46	26	230	10	0.43	<5	61	0.24	48	<10	54
B380718		2.77	0.98	487	1	0.26	37	300	12	0.59	<5	55	0.33	84	<10	92
B380719		1.93	0.62	260	1	0.13	25	240	19	0.49	5	43	0.24	66	<10	73
B380720		1.22	1.00	542	<1	0.06	21	200	14	0.10	14	62	0.24	51	<10	72
B380721		2.88	1.16	449	<1	0.14	41	470	26	0.53	<5	61	0.45	122	<10	86
B380722		3.02	1.31	481	1	0.15	51	500	25	0.61	<5	64	0.49	125	10	100
B380723		2.81	1.26	562	6	0.22	37	330	18	0.69	<5	62	0.37	108	<10	80
B380724		2.70	1.30	443	2	0.25	37	300	15	0.60	<5	58	0.36	85	<10	91
B380725		3.85	1.30	280	<1	0.20	40	410	23	0.34	<5	58	0.45	114	<10	98
B380726		2.97	1.31	385	<1	0.20	39	370	17	0.46	<5	69	0.37	94	<10	80
B380727		2.95	1.02	387	1	0.33	45	320	15	0.47	<5	50	0.38	97	10	90
B380728		1.80	0.86	365	<1	0.71	23	260	13	0.35	<5	85	0.26	60	<10	52
B380729																
B380730		2.30	0.62	399	9	0.12	498	340	158	0.02	12	51	0.25	96	30	643

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380731		5.76	<0.005	<0.5	7.97	42	570	2.0	<2	0.29	<0.5	12	142	45	4.51	<0.01
B380732		5.82	<0.005	<0.5	6.78	169	460	1.7	<2	0.48	<0.5	12	209	30	3.24	<0.01
B380733		6.46	<0.005	<0.5	5.62	58	390	1.1	<2	0.52	<0.5	9	148	32	2.52	<0.01
B380734		5.52	0.007	<0.5	6.38	92	400	1.4	<2	0.58	<0.5	14	170	36	3.16	<0.01
B380735		6.18	<0.005	<0.5	6.29	16	420	1.6	<2	0.70	<0.5	10	150	26	3.04	<0.01
B380736		1.74	<0.005	<0.5	0.13	5	20	<0.5	<2	20.0	<0.5	1	14	1	0.12	0.01
B380737		6.34	0.517	1.0	7.89	4640	710	2.1	57	0.37	<0.5	24	116	80	4.32	0.02
B380738		6.20	<0.005	<0.5	9.81	25	990	2.8	2	0.45	<0.5	17	144	52	4.41	0.01
B380739		6.06	<0.005	<0.5	9.18	28	850	2.3	<2	0.55	<0.5	15	130	44	4.92	0.01
B380740		5.52	<0.005	<0.5	9.14	14	730	2.2	<2	0.47	<0.5	15	132	34	4.11	0.01
B380741		2.58	0.005	<0.5	8.86	1950	740	2.1	2	0.53	<0.5	14	133	51	3.65	<0.01
B380742		2.60	0.007	<0.5	8.44	1330	640	2.1	<2	0.47	<0.5	12	152	41	3.56	0.01
B380743		6.00	0.008	<0.5	8.22	22	710	2.4	<2	0.72	<0.5	14	123	61	4.14	0.01
B380744		6.10	<0.005	<0.5	10.75	74	950	2.9	<2	0.49	<0.5	16	129	59	4.38	0.01
B380745		3.22	<0.005	<0.5	10.25	191	870	2.1	2	0.37	<0.5	17	130	61	4.00	0.01
B380746		1.66	<0.005	<0.5	7.79	1290	490	1.6	<2	0.10	<0.5	13	148	34	3.27	0.03
B380747		5.78	<0.005	<0.5	5.35	215	260	1.1	<2	0.07	<0.5	7	120	19	1.81	0.01
B380748		5.02	0.010	<0.5	4.27	656	180	0.8	<2	0.06	<0.5	6	178	58	1.92	0.02
B380749		0.04	0.009													
B380750		0.10	0.871	2.5	7.84	11	450	0.7	<2	1.95	0.7	23	106	2100	5.22	<0.01
B380751		5.90	<0.005	0.6	3.93	207	140	0.8	<2	0.08	<0.5	5	108	40	2.10	0.02
B380752		5.70	0.011	<0.5	3.61	808	90	0.8	<2	0.08	<0.5	4	138	19	1.76	0.02
B380753		6.04	<0.005	<0.5	7.74	45	460	1.9	<2	0.36	<0.5	11	109	29	3.77	0.01
B380754		5.36	0.005	<0.5	6.73	295	450	1.6	<2	0.54	<0.5	9	170	40	3.07	0.01
B380755		5.46	<0.005	<0.5	9.47	649	870	2.4	<2	0.55	<0.5	16	134	86	3.77	0.01
B380756		2.20	<0.005	<0.5	0.14	<5	20	<0.5	<2	18.55	<0.5	1	10	2	0.12	0.01
B380757		5.90	<0.005	<0.5	7.96	134	660	2.5	2	0.57	<0.5	16	122	48	3.50	<0.01
B380758		6.40	<0.005	<0.5	7.73	31	650	2.4	3	0.49	<0.5	13	118	38	3.61	0.01
B380759		5.58	0.008	<0.5	8.01	1980	630	2.0	<2	0.87	<0.5	15	139	69	3.59	0.01
B380760		5.94	<0.005	<0.5	8.57	17	780	2.9	2	0.51	<0.5	16	140	42	4.32	0.01
B380761		2.64	<0.005	<0.5	8.03	13	740	2.7	<2	0.46	<0.5	14	114	42	3.90	<0.01
B380762		2.00	<0.005	<0.5	8.14	11	720	2.6	<2	0.49	<0.5	15	148	52	4.05	0.01
B380763		6.86	<0.005	<0.5	8.95	5	730	2.7	2	0.27	<0.5	17	143	45	4.84	0.01
B380764		4.64	<0.005	<0.5	6.98	12	460	1.8	<2	0.15	<0.5	11	112	37	3.21	0.01
B380765		5.70	0.017	<0.5	3.70	1660	220	0.9	2	0.17	1.6	8	174	35	1.60	0.03
B380766		5.56	0.005	<0.5	4.74	67	290	1.2	2	0.16	<0.5	7	127	27	1.92	0.01
B380767		5.44	0.005	<0.5	2.59	116	120	0.6	<2	0.08	5.3	5	175	20	1.42	0.09
B380768		6.14	0.022	0.5	8.01	1855	740	1.8	<2	0.15	2.4	17	134	60	3.02	0.04
B380769		0.04	0.023													
B380770		0.10	0.429	2.5	8.66	<5	1020	1.2	2	1.42	<0.5	9	9	7230	3.11	0.03

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380731		2.47	1.21	263	1	0.39	37	300	17	0.61	<5	55	0.34	83	<10	80
B380732		1.99	0.87	215	1	0.78	31	300	13	0.38	<5	86	0.31	71	<10	64
B380733		1.78	0.75	200	1	0.70	22	240	8	0.27	<5	73	0.27	50	<10	43
B380734		1.82	0.82	299	1	0.75	26	270	6	0.52	<5	74	0.27	58	<10	54
B380735		1.73	0.88	392	<1	0.84	22	280	15	0.47	<5	96	0.28	58	<10	57
B380736		0.03	11.70	166	<1	0.01	9	510	<2	0.02	<5	111	<0.01	2	<10	9
B380737		2.99	0.94	218	1	0.33	44	300	127	1.42	84	69	0.25	80	<10	41
B380738		3.65	1.23	417	1	0.37	44	410	21	0.94	5	102	0.42	112	<10	80
B380739		3.28	1.40	512	<1	0.49	39	330	22	0.63	<5	99	0.37	91	<10	62
B380740		2.98	1.06	336	<1	0.15	38	290	17	0.31	<5	106	0.37	89	<10	85
B380741		3.24	1.10	248	1	0.47	38	300	19	0.62	6	81	0.33	88	<10	51
B380742		2.80	1.04	267	<1	0.44	34	290	17	0.47	<5	74	0.30	78	<10	53
B380743		2.78	1.08	443	6	0.65	37	330	22	0.87	<5	105	0.35	89	<10	69
B380744		3.96	1.07	253	<1	0.18	42	430	23	0.62	<5	90	0.43	113	<10	88
B380745		3.66	0.88	372	<1	0.13	47	350	21	0.53	9	62	0.39	106	<10	90
B380746		2.37	0.57	403	<1	0.10	29	300	5	0.23	21	57	0.31	76	10	64
B380747		1.11	0.27	209	1	0.04	20	180	5	0.13	<5	21	0.22	44	<10	44
B380748		0.94	0.21	182	1	0.03	17	200	3	0.72	5	14	0.17	34	<10	24
B380749																
B380750		1.82	1.37	441	2	3.23	52	680	15	0.63	<5	218	0.31	94	<10	212
B380751		0.71	0.28	208	<1	0.03	13	160	3	0.53	<5	15	0.15	30	<10	34
B380752		0.37	0.24	246	<1	0.02	10	150	10	0.16	<5	24	0.17	24	<10	32
B380753		1.64	0.78	269	<1	0.15	28	300	5	0.37	<5	55	0.32	70	<10	65
B380754		2.03	0.84	225	<1	0.50	24	270	3	0.38	<5	75	0.26	59	<10	61
B380755		3.83	1.14	223	1	0.15	39	360	6	0.91	<5	71	0.35	106	<10	67
B380756		0.04	11.45	152	<1	0.01	5	450	3	0.02	<5	110	0.01	3	<10	8
B380757		3.18	1.12	262	<1	0.17	39	300	12	0.41	<5	79	0.37	86	<10	74
B380758		2.76	1.13	260	1	0.16	36	290	16	0.48	<5	67	0.34	79	<10	74
B380759		3.32	1.37	293	1	0.21	41	360	16	0.68	<5	83	0.32	86	<10	60
B380760		3.33	1.20	399	1	0.24	42	330	21	0.85	6	72	0.33	95	<10	73
B380761		3.18	1.22	275	1	0.15	38	340	21	0.54	8	61	0.33	95	<10	70
B380762		3.00	1.24	303	1	0.14	42	340	24	0.65	<5	61	0.35	96	<10	91
B380763		2.96	1.30	227	1	0.19	47	350	24	0.43	<5	68	0.41	94	<10	102
B380764		1.84	0.64	265	1	0.09	31	290	12	0.59	8	40	0.30	65	<10	58
B380765		1.20	0.26	181	1	0.04	16	180	56	0.36	5	24	0.15	30	10	228
B380766		1.23	0.38	178	1	0.23	19	210	14	0.25	7	35	0.22	37	<10	46
B380767		0.82	0.24	202	1	0.02	12	190	47	0.23	6	13	0.11	20	<10	726
B380768		3.43	0.61	191	1	0.14	37	340	53	0.73	8	63	0.30	90	<10	380
B380769																
B380770		3.65	1.14	460	3	3.20	10	1830	11	0.23	<5	661	0.33	161	<10	57

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380771		6.04	0.011	<0.5	2.98	29	190	0.8	<2	0.10	<0.5	7	169	51	1.94	0.01
B380772		1.84	<0.005	<0.5	7.14	72	570	2.1	2	0.25	<0.5	11	152	122	3.26	0.01
B380773		2.14	<0.005	<0.5	8.74	23	730	2.4	3	0.21	<0.5	16	176	69	3.62	0.02
B380774		1.24	<0.005	<0.5	0.73	<5	20	<0.5	<2	0.03	<0.5	1	106	7	0.56	0.01
B380775		2.48	<0.005	<0.5	1.52	13	50	<0.5	<2	0.06	0.8	4	224	16	1.11	0.03
B380776		1.14	<0.005	<0.5	0.13	<5	10	<0.5	<2	16.75	<0.5	<1	8	2	0.10	<0.01
B380777		3.06	<0.005	<0.5	10.15	6	900	2.7	4	0.17	<0.5	17	145	49	3.47	0.01
B380778		5.90	0.006	<0.5	5.86	13	420	1.5	<2	0.34	<0.5	12	133	35	3.15	<0.01
B380779		4.54	0.005	<0.5	4.75	14	280	0.9	<2	1.18	<0.5	6	180	37	2.65	0.01
B380780		6.06	0.005	<0.5	4.92	188	290	1.0	<2	0.62	<0.5	7	116	69	2.34	<0.01
B380781		3.02	0.035	0.5	8.40	1450	730	2.4	4	0.44	<0.5	17	74	114	3.51	0.01
B380782		2.26	0.025	0.6	8.71	713	780	2.4	2	0.38	<0.5	14	99	106	3.53	0.01
B380783		3.44	<0.005	<0.5	7.15	10	530	1.8	<2	0.43	<0.5	13	164	27	3.33	0.01
B380784		2.08	0.008	<0.5	3.06	355	170	0.8	<2	0.69	<0.5	6	114	35	1.50	<0.01
B380785		7.16	<0.005	<0.5	7.72	753	560	1.9	2	0.53	<0.5	13	146	46	3.33	0.02
B380786		6.12	<0.005	<0.5	7.92	11	620	2.3	<2	0.41	<0.5	14	114	41	4.11	0.01
B380787		6.10	<0.005	<0.5	8.58	10	660	2.2	<2	0.35	<0.5	15	134	33	3.18	0.01
B380788		6.00	<0.005	<0.5	7.69	15	610	2.0	2	0.40	<0.5	13	112	36	3.62	<0.01
B380789		0.04	0.005													
B380790		0.10	0.092	0.5	6.61	97	530	2.5	<2	0.48	<0.5	54	1130	377	7.89	0.03
B380791		5.72	<0.005	<0.5	7.85	11	670	2.3	<2	0.35	<0.5	15	145	34	3.71	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060561

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380771		0.90	0.27	194	<1	0.04	14	190	9	0.49	5	21	0.13	28	<10	30
B380772		2.33	0.58	263	1	0.12	34	850	9	0.80	7	48	0.36	86	<10	68
B380773		3.24	0.73	246	1	0.18	40	350	22	0.67	9	61	0.35	97	<10	128
B380774		0.12	0.05	88	<1	<0.01	3	50	2	0.07	<5	5	0.03	3	<10	9
B380775		0.46	0.10	164	1	0.01	10	160	64	0.21	<5	12	0.09	10	<10	129
B380776		0.03	10.50	129	<1	0.01	4	420	<2	0.01	<5	100	<0.01	2	<10	7
B380777		3.74	0.68	247	1	0.21	45	350	26	0.60	10	70	0.45	118	<10	93
B380778		1.79	0.72	291	<1	0.20	28	280	11	0.41	5	37	0.24	56	<10	53
B380779		1.05	0.68	457	1	0.81	19	220	12	0.28	<5	106	0.20	35	<10	45
B380780		1.46	0.60	233	<1	0.79	19	200	12	0.41	<5	74	0.19	40	<10	43
B380781		3.76	1.02	207	3	0.20	50	360	24	0.90	<5	66	0.31	99	<10	93
B380782		3.96	1.02	190	3	0.19	45	360	20	0.89	<5	63	0.33	102	<10	63
B380783		2.33	0.95	266	1	0.53	33	260	13	0.38	<5	77	0.33	68	<10	71
B380784		0.88	0.44	197	1	0.32	14	190	8	0.28	<5	47	0.13	25	<10	20
B380785		2.59	0.98	314	1	0.40	33	270	15	0.53	<5	81	0.30	75	<10	66
B380786		2.75	1.12	324	<1	0.36	37	310	13	0.59	<5	83	0.34	83	<10	74
B380787		2.99	0.86	251	<1	0.52	37	280	19	0.45	<5	94	0.36	81	<10	61
B380788		2.64	1.00	289	<1	0.52	35	310	14	0.41	<5	94	0.34	74	<10	70
B380789																
B380790		2.13	0.56	351	7	0.11	462	320	144	0.02	11	49	0.19	81	30	580
B380791		2.87	0.99	246	1	0.46	37	340	16	0.49	<5	95	0.36	87	<10	83

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D. 2-AUG-2005
Account: STRGOL

CERTIFICATE VA05060560

Project: Dublin Gulch-1735

P.O. No.:

This report is for 45 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 22-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060560

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380792		0.38	<0.005	0.5	7.32	56	600	1.3	<2	0.95	<0.5	14	158	40	3.40	0.02
B380793		2.14	0.241	0.5	3.60	124	340	0.6	2	1.07	<0.5	8	166	23	2.24	0.03
B380794		1.90	0.165	12.2	4.47	582	260	0.9	3	1.66	<0.5	10	115	75	3.90	0.07
B380795		1.40	0.174	<0.5	1.52	100	80	<0.5	4	0.02	<0.5	2	196	41	1.36	0.04
B380796		1.64	<0.005	<0.5	0.12	<5	10	<0.5	<2	20.0	<0.5	<1	7	2	0.11	<0.01
B380797		3.02	0.090	<0.5	2.37	26	90	<0.5	<2	0.22	<0.5	6	160	25	2.02	0.10
B380798		4.02	0.021	<0.5	1.69	11	70	<0.5	<2	0.06	<0.5	1	83	15	1.19	0.04
B380799		4.16	0.019	<0.5	2.03	14	100	<0.5	<2	0.03	<0.5	3	108	18	1.29	0.08
B380800		4.26	0.374	<0.5	1.64	69	60	<0.5	4	0.03	<0.5	2	82	48	1.68	0.16
B380801		2.46	0.845	<0.5	1.82	3660	50	<0.5	10	0.02	<0.5	7	146	46	1.75	0.04
B380802		2.26	0.636	<0.5	1.72	1735	50	<0.5	8	0.02	<0.5	5	97	47	1.61	0.07
B380803		2.48	0.053	<0.5	2.00	63	30	<0.5	<2	0.03	<0.5	4	127	28	1.74	0.17
B380804		2.30	0.040	<0.5	1.84	40	80	<0.5	<2	0.02	<0.5	3	77	26	1.52	0.16
B380805		3.54	0.009	<0.5	3.04	16	150	0.6	<2	0.60	<0.5	9	131	55	2.49	0.53
B380806		3.10	0.007	<0.5	1.72	16	60	<0.5	<2	0.02	<0.5	3	102	20	2.13	0.39
B380807		4.38	<0.005	<0.5	1.82	8	40	<0.5	<2	0.02	<0.5	4	117	10	2.10	0.10
B380808		4.00	0.023	<0.5	3.60	34	210	1.0	<2	0.04	<0.5	10	100	43	3.42	0.53
B380809		0.04	0.021													
B380810		0.10	2.82	<0.5	7.73	2100	740	13.2	<2	0.01	<0.5	<1	136	104	3.51	0.08
B380811		6.98	0.034	<0.5	1.65	50	60	<0.5	<2	0.02	<0.5	2	90	16	1.34	0.03
B380812		2.44	0.092	<0.5	5.89	1385	400	1.2	2	0.05	<0.5	14	138	13	3.14	0.05
B380813		2.10	0.008	<0.5	1.80	124	50	<0.5	<2	0.02	<0.5	2	96	8	1.52	0.12
B380814		2.22	0.009	<0.5	1.82	14	60	<0.5	<2	0.02	<0.5	2	113	6	1.28	0.05
B380815		2.76	0.254	<0.5	1.96	349	130	<0.5	3	0.04	<0.5	6	116	55	2.46	0.04
B380816		1.74	<0.005	<0.5	0.11	5	10	<0.5	<2	19.85	<0.5	<1	13	6	0.09	<0.01
B380817		3.94	0.014	<0.5	1.67	39	120	<0.5	<2	0.06	<0.5	2	138	14	1.30	0.04
B380818		2.68	0.036	<0.5	1.80	128	120	<0.5	<2	0.03	<0.5	2	104	24	1.86	0.31
B380819		1.90	<0.005	<0.5	3.02	16	230	1.0	<2	0.04	<0.5	5	114	20	1.96	0.21
B380820		1.62	0.007	<0.5	2.23	12	140	0.7	<2	0.04	<0.5	4	100	19	1.76	0.29
B380821		1.12	0.053	<0.5	1.57	24	50	<0.5	<2	0.03	<0.5	3	132	22	1.39	0.53
B380822		1.12	0.038	<0.5	1.56	39	50	<0.5	<2	0.02	<0.5	2	84	17	1.26	0.46
B380823		4.90	<0.005	<0.5	1.73	25	90	<0.5	<2	0.03	<0.5	3	118	10	1.11	0.08
B380824		2.18	<0.005	<0.5	1.84	43	110	<0.5	<2	0.02	<0.5	2	110	18	1.46	0.18
B380825		1.82	0.167	<0.5	3.02	1365	380	0.8	2	0.11	<0.5	9	146	46	5.32	0.26
B380826		1.98	0.259	<0.5	7.37	2580	390	2.0	2	0.27	<0.5	26	560	59	10.50	0.25
B380827		2.80	0.015	<0.5	3.08	190	160	0.8	2	0.07	<0.5	9	188	75	3.91	0.48
B380828		3.54	<0.005	<0.5	1.65	31	80	<0.5	<2	0.02	<0.5	2	77	12	1.56	0.13
B380829		0.04	<0.005													
B380830		0.10	3.43	0.7	7.09	6	2010	3.2	<2	4.67	<0.5	23	135	94	5.02	<0.01
B380831		1.02	0.024	<0.5	4.00	218	270	1.0	<2	0.12	<0.5	10	293	35	4.96	0.25

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060560

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380792		2.59	0.96	493	<1	0.38	34	240	24	0.11	17	154	0.39	105	10	87
B380793		0.95	0.61	347	<1	0.55	25	230	17	0.28	5	82	0.15	40	10	45
B380794		1.28	1.07	509	<1	0.73	29	280	34	1.48	53	200	0.23	66	<10	45
B380795		0.57	0.06	121	1	0.01	13	60	3	0.73	<5	14	0.07	13	<10	11
B380796		0.03	12.05	159	<1	0.01	5	570	<2	0.01	<5	117	<0.01	2	<10	7
B380797		0.34	0.22	400	<1	0.08	20	220	6	0.25	6	40	0.13	26	<10	41
B380798		0.51	0.08	233	<1	0.01	10	70	7	0.32	<5	16	0.06	13	<10	14
B380799		0.60	0.09	273	<1	0.01	12	90	7	0.30	<5	17	0.07	17	<10	26
B380800		0.35	0.07	239	<1	0.01	11	100	5	0.70	<5	18	0.08	15	<10	17
B380801		0.37	0.06	210	<1	0.01	13	70	6	0.77	7	17	0.09	17	<10	19
B380802		0.36	0.05	178	<1	0.01	12	60	5	0.85	7	17	0.09	16	<10	16
B380803		0.17	0.06	370	<1	<0.01	14	80	3	0.30	8	19	0.09	18	10	36
B380804		0.48	0.09	305	<1	0.01	11	90	6	0.37	<5	18	0.06	14	<10	27
B380805		0.72	0.45	497	<1	0.11	27	190	8	0.60	<5	57	0.14	40	<10	55
B380806		0.36	0.09	548	<1	0.01	9	70	2	0.26	<5	20	0.06	15	<10	37
B380807		0.26	0.08	609	<1	<0.01	8	90	3	0.08	<5	25	0.07	15	<10	42
B380808		1.08	0.22	817	<1	0.02	22	200	4	0.59	5	40	0.16	45	<10	53
B380809																
B380810		3.32	0.39	71	1	0.09	10	340	34	0.02	156	146	0.25	107	10	17
B380811		0.49	0.07	265	<1	0.01	8	100	4	0.25	<5	21	0.07	13	<10	21
B380812		1.56	0.32	715	<1	0.03	37	230	9	0.17	13	61	0.26	93	<10	78
B380813		0.32	0.07	375	<1	0.01	13	110	2	0.08	5	38	0.09	17	<10	22
B380814		0.33	0.09	279	<1	0.01	11	100	2	0.07	8	31	0.10	18	<10	26
B380815		0.68	0.08	408	<1	0.01	13	190	3	0.93	6	81	0.11	19	<10	17
B380816		0.03	12.10	150	<1	0.01	4	490	3	0.01	<5	110	<0.01	2	<10	13
B380817		0.54	0.11	274	<1	0.01	11	130	2	0.14	<5	60	0.09	16	<10	23
B380818		0.45	0.10	330	<1	0.01	11	130	5	0.45	5	67	0.08	17	<10	21
B380819		0.90	0.22	334	<1	0.02	18	170	9	0.22	<5	68	0.14	34	<10	48
B380820		0.61	0.16	362	<1	0.01	12	130	7	0.20	<5	52	0.09	23	<10	35
B380821		0.24	0.07	310	<1	0.01	10	140	4	0.26	<5	78	0.07	13	<10	22
B380822		0.24	0.07	304	<1	0.01	9	140	2	0.18	<5	84	0.06	12	<10	21
B380823		0.45	0.10	243	<1	0.01	9	130	3	0.14	<5	57	0.07	14	<10	22
B380824		0.55	0.12	294	<1	0.01	10	90	3	0.27	5	45	0.06	16	<10	18
B380825		1.12	0.31	1320	<1	0.01	20	1040	7	0.48	16	631	0.09	31	<10	39
B380826		1.78	0.80	2820	<1	0.03	70	1390	10	0.78	58	634	0.28	122	10	122
B380827		0.90	0.28	721	<1	0.01	35	230	6	1.15	17	99	0.11	40	<10	46
B380828		0.41	0.11	325	<1	0.01	9	120	4	0.32	5	64	0.06	14	<10	18
B380829																
B380830		3.40	2.91	1015	12	2.31	68	2320	30	0.30	<5	1640	0.37	164	10	94
B380831		1.32	0.49	1180	<1	0.02	35	490	5	0.65	19	192	0.16	61	<10	47

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060560

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380832		4.26	0.116	<0.5	1.78	21	60	<0.5	<2	0.03	<0.5	4	136	59	2.32	0.36
B380833		3.16	0.008	<0.5	2.02	23	230	<0.5	<2	0.08	<0.5	2	104	18	2.80	0.03
B380834		2.52	<0.005	<0.5	1.73	7	90	<0.5	<2	0.02	<0.5	2	114	10	1.09	0.04
B380835		1.34	<0.005	<0.5	12.85	56	1640	2.9	<2	0.19	<0.5	23	190	44	5.75	0.15
B380836		1.62	<0.005	<0.5	0.19	<5	20	<0.5	<2	20.1	<0.5	<1	13	2	0.11	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 2-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060560

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380832		0.28	0.12	462	<1	0.01	13	80	4	0.59	11	38	0.07	17	10	23
B380833		0.48	0.15	770	<1	0.01	10	1240	6	0.04	12	780	0.05	19	<10	21
B380834		0.39	0.10	222	<1	0.01	11	130	4	0.05	<5	62	0.06	14	<10	25
B380835		5.86	1.00	760	<1	0.18	55	840	13	0.67	11	51	0.76	256	10	265
B380836		0.06	11.90	163	<1	0.01	5	600	3	0.01	<5	116	0.01	3	<10	7

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D. 3-AUG-2005
Account: STRGOL

CERTIFICATE VA05060214

Project: Dublin Gulch-1735

P.O. No.:

This report is for 117 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 22-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B382217		4.56	0.250		0.5	7.30	124	1180	2.9	<2	2.67	<0.5	8	25	27	2.06
B382218		3.82	0.059		<0.5	7.07	174	1410	2.7	<2	2.42	<0.5	9	45	21	1.92
B382219		5.98	0.173		<0.5	7.61	111	1520	2.9	<2	2.27	<0.5	8	25	28	2.26
B382220		6.10	0.218		<0.5	7.13	213	1230	2.7	8	3.41	<0.5	9	44	32	1.96
B382221		2.54	0.146		<0.5	7.72	178	1700	3.0	4	2.22	<0.5	10	29	24	2.67
B382222		2.12	0.047		<0.5	7.75	95	1690	3.2	<2	2.69	<0.5	9	54	16	2.51
B382223		5.78	0.089		<0.5	7.68	113	1710	3.1	<2	2.43	<0.5	9	32	26	2.58
B382224		6.76	0.085		<0.5	8.04	200	1620	3.2	5	2.32	<0.5	10	58	37	2.47
B382225		5.40	0.084		<0.5	8.03	114	1600	3.1	<2	2.39	<0.5	9	31	21	2.54
B382226		6.10	0.072		<0.5	7.28	192	1520	3.0	<2	2.20	<0.5	8	60	25	2.25
B382227		5.50	0.123		<0.5	7.88	226	1630	2.8	<2	2.32	<0.5	9	28	25	2.44
B382228		1.74	0.016		<0.5	7.70	18	1650	2.8	<2	1.98	<0.5	9	59	23	2.50
B382229		0.04	0.102													
B382230		0.12	2.90		<0.5	8.25	2290	800	13.6	<2	0.01	<0.5	1	162	110	3.68
B382231		4.16	0.275		<0.5	7.88	96	1690	3.0	28	2.47	<0.5	10	62	35	2.45
B382232		3.34	0.292		<0.5	8.22	126	1640	3.4	<2	2.33	<0.5	12	29	39	2.60
B382233		3.86	0.099		<0.5	7.87	123	1500	3.1	2	2.22	<0.5	9	64	36	2.41
B382234		3.30	1.990		<0.5	7.45	131	1520	2.8	29	2.27	<0.5	11	31	47	2.56
B382235		3.40	0.477		<0.5	8.43	129	1790	3.1	12	2.58	<0.5	11	66	43	2.75
B382236		1.68	<0.005		<0.5	0.15	5	20	<0.5	<2	19.20	<0.5	1	2	1	0.17
B382237		1.06	0.366		<0.5	7.60	50	1660	3.0	<2	2.11	<0.5	9	62	41	2.49
B382238		5.38	0.111		<0.5	7.80	122	1360	3.0	5	2.17	<0.5	9	27	41	2.52
B382239		5.24	0.097		<0.5	8.00	224	1570	3.1	<2	2.25	<0.5	10	60	45	2.51
B382240		3.26	0.521		<0.5	8.09	938	1630	3.1	18	2.35	<0.5	11	33	64	2.62
B382241		1.42	0.127		0.6	7.75	231	1480	2.9	<2	2.22	<0.5	11	68	46	2.36
B382242		1.16	0.119		<0.5	7.70	227	1460	2.8	<2	2.23	<0.5	9	27	53	2.26
B382243		2.24	0.143		<0.5	8.17	489	1660	3.1	5	2.58	<0.5	10	65	58	2.39
B382244		4.76	0.087		<0.5	6.94	217	1490	2.8	<2	2.62	<0.5	9	26	70	2.37
B382245		3.52	0.100		<0.5	7.18	302	1310	3.1	<2	2.52	<0.5	8	60	36	2.16
B382246		3.04	0.062		<0.5	7.85	257	1480	3.0	<2	2.10	<0.5	8	27	21	2.34
B382247		5.80	1.375		<0.5	6.89	229	1440	2.9	10	2.33	<0.5	10	54	30	2.13
B382248		2.76	0.093		<0.5	8.43	226	1800	3.3	<2	2.64	<0.5	11	32	25	2.74
B382249		0.04	0.076													
B382250		0.12	4.47		9.8	8.26	10	510	1.0	<2	2.97	0.9	20	22	124	4.28
B382251		3.26	0.322		<0.5	8.01	115	1560	3.1	5	2.64	<0.5	9	24	34	2.40
B382252		7.08	0.257		<0.5	7.94	650	1730	3.2	6	2.40	<0.5	10	56	37	2.46
B382253		6.76	0.175		<0.5	8.20	320	1710	3.2	2	2.36	<0.5	9	29	36	2.64
B382254		7.08	0.063		<0.5	7.09	216	1460	3.1	<2	2.28	<0.5	9	52	16	2.25
B382255		5.66	0.172		<0.5	7.65	441	1560	3.1	<2	2.33	<0.5	9	32	28	2.67
B382256		2.00	<0.005		<0.5	0.14	<5	20	<0.5	<2	21.0	<0.5	1	8	1	0.14

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method Analyte Units LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B382217		0.02	3.82	0.68	350	<1	1.11	17	570	56	0.28	17	343	0.27	33	20
B382218		0.01	3.93	0.52	262	1	1.53	19	590	27	0.11	10	344	0.27	34	30
B382219		0.01	3.98	0.68	276	3	1.38	19	580	25	0.23	12	358	0.28	35	20
B382220		0.02	3.75	0.59	390	1	1.20	20	600	75	0.29	26	317	0.29	35	20
B382221		0.01	3.80	0.88	296	1	1.70	22	610	25	0.17	<5	480	0.32	40	20
B382222		0.01	3.83	0.90	331	1	1.62	25	660	23	0.13	6	493	0.33	40	30
B382223		0.01	3.78	0.93	308	3	1.76	23	660	25	0.14	<5	542	0.33	40	30
B382224		0.01	4.07	0.87	286	2	1.86	24	630	27	0.17	<5	546	0.32	37	30
B382225		0.01	3.78	0.92	314	2	1.83	20	630	24	0.12	<5	534	0.32	39	10
B382226		0.01	3.75	0.78	256	3	1.68	20	590	24	0.14	<5	497	0.29	37	20
B382227		0.02	4.24	0.92	308	2	1.68	22	640	23	0.11	6	505	0.31	37	30
B382228		0.02	3.77	0.99	293	2	1.58	23	600	27	0.09	<5	488	0.32	40	20
B382229																
B382230		0.09	3.63	0.41	75	2	0.10	11	360	29	0.02	179	161	0.23	114	10
B382231		0.01	4.02	0.79	256	2	1.73	23	660	26	0.22	5	497	0.32	40	20
B382232		0.01	4.12	0.82	275	1	1.85	26	630	24	0.13	<5	516	0.31	38	20
B382233		0.01	4.09	0.83	263	2	1.74	22	590	25	0.15	<5	499	0.29	35	50
B382234		<0.01	3.79	0.84	259	1	1.66	20	600	18	0.17	6	502	0.30	36	50
B382235		0.01	4.31	0.95	299	1	1.90	22	710	24	0.19	<5	584	0.35	43	70
B382236		<0.01	0.04	11.20	165	<1	0.01	4	460	<2	0.02	<5	112	<0.01	<1	<10
B382237		0.01	3.77	0.88	251	1	1.72	20	670	20	0.14	<5	500	0.32	39	20
B382238		0.01	3.93	0.77	236	1	1.68	24	660	23	0.17	<5	410	0.31	38	20
B382239		0.01	3.97	0.86	269	2	1.75	23	640	21	0.24	<5	517	0.31	38	30
B382240		0.01	4.21	0.84	268	9	1.70	23	680	24	0.30	<5	519	0.32	37	40
B382241		0.01	3.95	0.74	244	2	1.65	22	620	25	0.30	<5	461	0.30	38	20
B382242		0.01	3.87	0.69	231	1	1.67	22	630	21	0.36	7	438	0.29	35	20
B382243		0.01	4.31	0.85	240	1	1.76	20	680	23	0.24	<5	532	0.32	39	20
B382244		0.03	3.75	0.97	313	<1	1.40	20	610	23	0.18	<5	489	0.29	36	30
B382245		0.03	3.82	0.73	288	1	1.54	20	570	31	0.31	7	423	0.27	35	20
B382246		0.01	4.04	0.89	268	1	1.69	21	590	22	0.13	<5	503	0.30	35	30
B382247		0.01	3.86	0.79	267	1	1.60	19	570	27	0.13	<5	489	0.28	33	20
B382248		0.01	4.00	0.93	332	1	1.95	24	720	28	0.13	<5	611	0.35	43	30
B382249																
B382250		0.01	2.44	1.40	1020	13	1.75	11	930	24	0.72	<5	435	0.39	156	<10
B382251		0.01	4.15	0.94	291	1	1.40	20	630	29	0.19	8	472	0.30	36	30
B382252		0.01	4.11	0.91	294	2	1.55	24	680	33	0.16	<5	497	0.32	39	20
B382253		0.01	3.86	0.98	324	3	1.78	24	680	32	0.12	<5	549	0.33	39	20
B382254		0.01	3.67	0.83	320	1	1.74	19	570	29	0.07	<5	495	0.29	34	20
B382255		0.01	3.69	0.80	299	6	1.68	20	600	29	0.18	<5	494	0.30	36	20
B382256		<0.01	0.05	11.70	190	<1	0.02	2	510	<2	<0.01	<5	118	<0.01	1	<10

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B382217		98
B382218		59
B382219		58
B382220		122
B382221		56
B382222		56
B382223		64
B382224		63
B382225		64
B382226		52
B382227		61
B382228		62
B382229		
B382230		18
B382231		45
B382232		58
B382233		52
B382234		48
B382235		58
B382236		6
B382237		51
B382238		54
B382239		57
B382240		54
B382241		50
B382242		47
B382243		39
B382244		47
B382245		51
B382246		51
B382247		50
B382248		69
B382249		
B382250		104
B382251		51
B382252		70
B382253		63
B382254		63
B382255		58
B382256		7

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B382257		6.48	0.060		<0.5	7.52	345	1580	3.0	<2	2.51	<0.5	10	32	25	2.59
B382258		3.96	7.76	0.219	<0.5	7.53	545	1530	2.7	5	2.24	<0.5	7	62	21	2.45
B382259		3.16	0.105	0.118	0.7	7.07	289	1230	2.9	<2	3.10	1.0	9	31	39	2.31
B382260		7.36	0.938	0.319	<0.5	7.61	842	1560	3.0	18	2.57	<0.5	9	76	33	2.57
B382261		3.30	0.200		<0.5	7.78	569	1560	3.1	6	2.25	<0.5	10	30	49	2.60
B382262		3.04	0.323		<0.5	7.52	771	1520	3.1	10	2.16	<0.5	11	61	48	2.37
B382263		5.76	0.391		0.7	7.66	625	1640	2.9	5	2.28	<0.5	10	31	50	2.51
B382264		6.58	0.080		<0.5	7.59	363	1530	3.0	2	2.28	<0.5	9	51	38	2.34
B382265		5.16	0.122		<0.5	7.34	216	1510	2.9	4	2.27	<0.5	9	30	36	2.28
B382266		6.76	0.071		<0.5	7.33	482	1490	3.0	<2	2.39	<0.5	10	62	64	2.34
B382267		6.64	0.086		<0.5	7.43	109	1620	3.1	<2	2.53	<0.5	10	30	48	2.50
B382268		6.30	0.060		<0.5	7.47	385	1540	2.7	<2	2.06	<0.5	9	28	55	2.32
B382269		0.04	0.080													
B382270		0.10	0.094		<0.5	6.85	112	570	2.7	<2	0.52	<0.5	61	1210	388	8.26
B382271		5.78	0.189		<0.5	7.85	322	1500	3.1	<2	2.24	<0.5	9	29	38	2.38
B382272		6.30	0.122		<0.5	7.38	279	1560	2.9	<2	2.53	<0.5	10	30	57	2.54
B382273		6.76	0.235		<0.5	7.52	297	1410	3.0	<2	2.34	<0.5	8	26	42	2.24
B382274		5.74	0.052		<0.5	6.83	150	1140	3.2	<2	2.07	<0.5	8	21	39	1.86
B382275		5.92	0.197		<0.5	7.33	206	1430	2.9	<2	2.18	<0.5	8	24	80	2.20
B382276		2.08	<0.005		<0.5	0.17	5	20	<0.5	<2	20.0	<0.5	1	3	1	0.12
B382277		6.34	0.044		<0.5	7.80	138	1620	3.1	<2	2.65	<0.5	10	30	44	2.56
B382278		4.12	0.509		0.7	7.67	129	1620	3.0	102	2.68	<0.5	10	32	65	2.44
B382279		2.64	0.129		0.6	7.47	184	1600	3.1	<2	2.32	<0.5	10	31	43	2.49
B382280		6.02	0.231		0.5	7.78	194	1590	3.0	6	2.42	<0.5	10	30	57	2.54
B382281		2.20	0.052		<0.5	7.85	244	1680	3.3	<2	2.51	<0.5	10	29	54	2.54
B382282		2.36	0.154		<0.5	7.84	377	1640	3.2	<2	2.51	<0.5	11	27	72	2.54
B382283		6.92	0.118		<0.5	8.03	639	1600	3.2	5	2.25	<0.5	11	30	78	2.49
B382284		6.18	0.064		<0.5	7.35	170	1420	3.2	<2	2.25	<0.5	9	27	55	2.43
B382285		6.92	0.397		0.6	7.71	604	1640	3.0	9	2.52	1.9	11	29	90	2.67
B382286		6.30	0.025		<0.5	8.07	227	1690	3.1	<2	2.65	<0.5	10	30	27	2.63
B382287		6.66	0.037		<0.5	7.62	440	1390	2.9	<2	2.85	<0.5	9	29	42	2.42
B382288		6.24	0.030		<0.5	7.83	178	1580	3.1	<2	2.11	<0.5	9	28	22	2.48
B382289		0.04	0.053													
B382290		0.10	3.05		1.3	7.13	10	2120	3.3	<2	4.91	<0.5	27	147	100	5.10
B382291		6.32	0.138		<0.5	8.07	98	1720	3.0	<2	2.38	<0.5	10	29	56	2.63
B382292		5.92	0.079		<0.5	7.65	341	1450	3.4	<2	2.07	<0.5	9	26	41	2.27
B382293		6.06	0.125		<0.5	6.94	53	1530	2.9	<2	2.32	<0.5	10	29	42	2.38
B382294		6.54	0.053		0.5	7.42	265	970	2.9	<2	2.71	0.7	9	27	42	2.37
B382295		5.94	0.091		0.9	6.60	379	910	2.6	<2	2.59	1.2	8	23	40	2.03
B382296		2.44	<0.005		<0.5	0.12	<5	20	<0.5	<2	20.3	<0.5	1	2	1	0.10

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B382257		0.01	3.80	0.84	304	2	1.78	20	620	29	0.16	<5	507	0.31	37	50
B382258		0.01	3.30	0.84	280	1	1.72	19	620	25	0.13	<5	497	0.27	32	10
B382259		0.03	3.61	0.52	500	3	0.94	20	590	105	0.30	24	294	0.28	36	70
B382260		0.01	3.79	0.81	293	2	1.67	22	630	33	0.24	7	492	0.31	37	30
B382261		0.01	3.82	0.81	241	1	1.70	18	620	22	0.26	<5	491	0.31	37	20
B382262		<0.01	3.88	0.77	211	2	1.64	21	600	22	0.27	<5	476	0.30	35	30
B382263		0.01	3.96	0.84	237	2	1.69	23	620	22	0.27	<5	502	0.31	37	30
B382264		0.01	3.71	0.80	270	1	1.70	22	620	30	0.16	<5	471	0.31	37	20
B382265		0.01	3.82	0.77	249	2	1.68	18	620	25	0.17	<5	479	0.30	36	30
B382266		0.01	3.94	0.77	240	3	1.67	23	630	22	0.29	<5	463	0.30	37	30
B382267		0.01	3.84	0.86	299	2	1.78	20	670	23	0.22	<5	512	0.32	40	60
B382268		0.01	3.61	0.78	218	5	1.56	19	620	23	0.33	<5	499	0.30	40	30
B382269																
B382270		0.03	2.29	0.58	382	8	0.12	473	340	146	0.02	11	50	0.19	92	30
B382271		0.01	3.86	0.82	239	1	1.73	24	590	23	0.19	<5	488	0.30	36	20
B382272		0.02	3.63	0.86	269	2	1.66	21	640	21	0.25	<5	466	0.31	38	10
B382273		0.01	3.97	0.76	252	2	1.74	19	550	26	0.21	<5	465	0.28	32	20
B382274		0.01	4.10	0.60	237	2	1.66	16	450	34	0.17	<5	387	0.23	27	10
B382275		0.01	4.31	0.78	219	1	1.66	18	560	25	0.24	<5	454	0.28	33	20
B382276		<0.01	0.05	11.45	159	<1	0.02	<1	510	3	0.01	<5	124	<0.01	1	<10
B382277		0.01	3.83	0.93	297	<1	1.89	22	670	23	0.20	<5	553	0.34	41	20
B382278		<0.01	3.97	0.86	253	3	1.82	22	660	26	0.28	<5	531	0.32	39	10
B382279		0.01	3.72	0.82	271	1	1.77	24	660	26	0.25	<5	511	0.32	38	10
B382280		0.01	3.75	0.91	261	1	1.77	22	660	21	0.28	<5	526	0.33	39	30
B382281		0.01	3.65	0.88	248	3	1.84	20	690	22	0.34	<5	540	0.33	42	10
B382282		0.01	3.71	0.89	248	5	1.82	22	670	18	0.38	<5	540	0.33	40	10
B382283		0.01	4.48	0.82	209	2	1.72	20	620	19	0.39	<5	512	0.31	38	20
B382284		0.01	3.88	0.69	274	1	1.54	23	610	31	0.45	15	379	0.28	35	10
B382285		0.04	4.40	0.83	312	1	1.56	20	660	101	0.51	20	479	0.32	41	30
B382286		0.01	3.75	0.89	347	2	1.91	22	680	33	0.15	<5	558	0.34	40	20
B382287		0.02	3.57	0.77	477	3	1.49	21	620	73	0.25	15	467	0.29	35	20
B382288		0.03	3.74	0.86	316	<1	1.60	23	650	42	0.12	10	471	0.32	38	20
B382289																
B382290		<0.01	3.62	2.98	1075	13	2.42	68	2350	33	0.32	<5	1675	0.37	170	10
B382291		0.02	4.02	0.94	326	<1	1.64	24	660	29	0.18	6	522	0.34	40	20
B382292		0.01	3.93	0.74	255	3	1.58	20	570	30	0.19	<5	441	0.28	35	10
B382293		0.03	3.60	0.78	289	1	1.52	21	630	24	0.20	7	444	0.31	37	20
B382294		0.04	3.68	0.50	428	1	0.72	25	640	104	0.36	30	206	0.30	38	20
B382295		0.05	3.38	0.54	489	<1	0.66	18	520	170	0.34	27	246	0.25	31	20
B382296		<0.01	0.04	11.45	162	<1	0.01	2	480	<2	<0.01	<5	112	<0.01	<1	<10

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B382257		60
B382258		49
B382259		288
B382260		60
B382261		39
B382262		36
B382263		41
B382264		62
B382265		51
B382266		48
B382267		51
B382268		39
B382269		
B382270		626
B382271		45
B382272		53
B382273		45
B382274		51
B382275		40
B382276		7
B382277		60
B382278		44
B382279		53
B382280		45
B382281		38
B382282		37
B382283		33
B382284		47
B382285		369
B382286		76
B382287		100
B382288		73
B382289		
B382290		100
B382291		72
B382292		55
B382293		46
B382294		271
B382295		348
B382296		7

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B382297		6.36	0.170		<0.5	6.42	331	1340	2.5	7	2.81	0.7	8	25	58	2.18
B382298		2.78	0.105		0.6	7.05	1140	1440	2.8	3	2.14	<0.5	9	29	63	2.28
B382299		2.38	0.245		1.0	6.44	1095	1120	2.7	5	2.45	<0.5	8	24	116	2.33
B382300		2.94	0.283		0.8	6.33	1180	1260	2.7	9	2.26	<0.5	10	23	99	2.19
B382301		1.58	0.078		0.6	6.47	476	1310	2.7	10	1.78	<0.5	6	26	45	1.96
B382302		1.56	0.116		<0.5	6.71	672	1310	2.7	18	2.08	<0.5	9	24	51	2.00
B382303		5.28	0.224		0.6	6.83	703	1330	2.8	10	1.95	<0.5	8	26	67	2.18
B382304		6.08	0.359		<0.5	7.09	230	1400	2.9	13	2.62	<0.5	9	28	58	2.41
B382305		6.04	0.092		<0.5	7.36	262	1520	2.8	9	2.09	<0.5	9	26	62	2.36
B382306		3.66	0.104		0.6	7.91	114	1470	3.1	<2	2.87	<0.5	9	29	54	2.33
B382307		2.86	0.099		<0.5	7.21	134	1340	2.9	21	2.54	<0.5	8	28	53	2.20
B382308		3.54	0.055		<0.5	7.49	370	1500	3.2	5	2.58	<0.5	9	30	56	2.35
B382309		0.04	0.066													
B382310		0.10	0.424		3.0	8.95	<5	1060	1.2	<2	1.49	<0.5	10	8	7150	3.15
B382311		2.94	0.278		0.6	6.99	367	1410	2.7	8	2.04	<0.5	11	29	114	2.40
B382312		2.68	0.113		<0.5	7.61	182	1620	3.2	6	2.49	<0.5	9	31	68	2.47
B382313		4.04	0.106		0.5	6.92	315	1460	2.5	16	2.26	<0.5	9	29	91	2.36
B382314		5.88	0.045		<0.5	7.49	110	1600	3.0	<2	2.15	<0.5	9	29	68	2.32
B382315		3.78	0.029		<0.5	7.26	37	1520	3.1	<2	2.31	<0.5	10	31	76	2.46
B382316		2.18	<0.005		<0.5	0.20	<5	20	<0.5	<2	20.5	<0.5	<1	3	1	0.15
B382317		2.24	0.132		<0.5	7.28	56	1460	3.2	7	2.14	<0.5	11	34	126	2.66
B382318		7.34	0.056		<0.5	7.38	188	1410	3.1	3	2.29	<0.5	10	39	69	2.64
B382319		6.80	0.093		<0.5	7.67	289	1420	3.1	9	2.79	<0.5	12	40	59	2.66
B382320		3.34	0.136		0.7	7.56	150	1380	3.1	6	2.13	<0.5	10	48	51	2.53
B382321		0.98	0.083		<0.5	7.16	56	1320	3.0	4	2.39	<0.5	9	37	56	2.49
B382322		0.82	0.133		<0.5	7.00	47	1320	3.2	6	2.16	<0.5	10	44	62	2.62
B382323		6.10	0.120		<0.5	7.07	97	1290	3.3	5	2.26	<0.5	9	37	57	2.46
B382324		5.92	0.216		0.7	6.68	288	1340	3.1	74	2.07	<0.5	9	39	65	2.46
B382325		6.42	0.170		0.6	7.02	281	1380	3.0	22	2.33	0.8	11	35	73	2.52
B382326		4.34	0.103		<0.5	6.96	92	1560	2.9	<2	2.54	<0.5	11	35	50	2.50
B382327		1.56	0.024		<0.5	7.82	5	1420	3.9	<2	2.20	<0.5	7	28	13	2.26
B382328		4.16	0.097		1.0	7.23	122	1400	3.5	2	2.18	1.8	15	30	77	2.37
B382329		0.04	0.177													
B382330		0.12	1.345		<0.5	6.52	1180	640	5.6	<2	0.01	<0.5	6	209	36	3.45
B382331		2.36	0.095		<0.5	6.82	242	1650	2.8	23	2.03	<0.5	13	28	97	2.37
B382332		2.02	0.133		<0.5	6.51	168	1320	2.4	9	1.92	<0.5	11	24	176	2.35
B382333		3.24	0.141		<0.5	7.02	126	1470	2.9	8	2.08	<0.5	10	26	77	2.16

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B382297		0.04	3.75	0.72	383	3	1.16	19	540	64	0.28	25	407	0.26	32	20
B382298		0.01	3.84	0.79	262	2	1.44	18	630	21	0.33	12	407	0.30	37	20
B382299		0.01	3.31	0.73	299	5	0.84	13	550	84	0.83	30	344	0.25	31	30
B382300		0.02	3.81	0.76	253	2	1.18	18	510	50	0.54	23	409	0.25	31	30
B382301		0.02	3.83	0.74	222	21	1.32	13	510	25	0.17	8	389	0.24	28	20
B382302		0.02	3.98	0.76	237	11	1.34	15	500	24	0.19	10	427	0.24	29	20
B382303		0.02	3.79	0.80	240	2	1.20	19	570	53	0.34	18	398	0.27	34	20
B382304		0.01	3.74	0.87	361	1	1.19	19	620	39	0.30	23	416	0.29	37	20
B382305		0.01	3.91	0.83	258	<1	1.65	20	590	24	0.26	13	466	0.29	35	10
B382306		0.01	4.04	0.78	320	1	1.46	23	690	37	0.30	9	424	0.34	41	10
B382307		0.01	3.67	0.67	270	1	1.61	20	630	29	0.25	12	400	0.29	36	30
B382308		<0.01	4.07	0.72	255	1	1.76	18	650	26	0.28	5	476	0.30	38	10
B382309																
B382310		0.03	3.79	1.14	482	2	3.41	8	1880	14	0.24	<5	676	0.34	175	<10
B382311		<0.01	4.13	0.73	180	1	1.46	16	590	21	0.49	5	425	0.27	37	40
B382312		<0.01	3.89	0.86	215	2	1.73	19	630	21	0.32	<5	528	0.31	37	10
B382313		<0.01	4.72	0.88	196	1	1.38	17	590	21	0.43	<5	487	0.28	35	20
B382314		0.01	4.08	0.85	206	2	1.60	23	610	20	0.25	<5	499	0.30	36	20
B382315		<0.01	4.00	0.86	227	<1	1.66	18	630	23	0.32	<5	502	0.30	37	10
B382316		<0.01	0.04	11.70	170	<1	0.02	4	590	<2	0.03	<5	120	<0.01	1	<10
B382317		<0.01	4.41	0.90	192	<1	1.68	13	630	20	0.54	<5	508	0.28	41	20
B382318		0.01	3.78	1.12	268	1	1.72	14	630	18	0.24	<5	520	0.30	49	20
B382319		0.01	3.76	1.11	333	1	1.68	16	660	19	0.26	<5	510	0.30	50	20
B382320		0.01	3.90	1.04	292	1	1.73	20	640	24	0.18	<5	498	0.31	62	10
B382321		0.01	3.61	1.14	311	1	1.60	12	630	17	0.21	<5	515	0.29	49	20
B382322		0.01	3.57	1.14	284	<1	1.66	13	630	21	0.22	<5	505	0.30	51	20
B382323		0.01	3.91	1.04	310	1	1.64	13	580	23	0.17	8	489	0.27	45	20
B382324		<0.01	3.66	1.12	301	1	1.55	14	620	22	0.18	12	485	0.30	48	20
B382325		0.02	3.80	1.04	363	3	1.50	14	600	51	0.29	16	459	0.28	44	20
B382326		0.01	3.69	0.89	336	1	1.60	20	670	22	0.29	12	477	0.32	45	10
B382327		<0.01	4.00	0.80	346	1	1.99	16	610	29	0.05	<5	486	0.27	36	<10
B382328		0.03	4.47	0.89	387	2	0.96	19	630	114	0.40	27	360	0.30	42	20
B382329																
B382330		0.05	2.68	0.32	83	2	0.10	19	290	22	0.02	112	89	0.18	86	10
B382331		<0.01	4.05	0.92	238	9	1.58	18	610	18	0.35	6	493	0.30	41	10
B382332		0.01	4.11	0.78	175	3	1.29	21	480	19	0.54	5	414	0.24	32	10
B382333		0.01	4.19	0.84	193	3	1.62	19	560	18	0.28	5	485	0.30	37	40

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 8-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060214

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B382297		233
B382298		36
B382299		99
B382300		39
B382301		33
B382302		31
B382303		80
B382304		80
B382305		42
B382306		71
B382307		60
B382308		63
B382309		
B382310		58
B382311		27
B382312		29
B382313		19
B382314		28
B382315		30
B382316		7
B382317		24
B382318		31
B382319		37
B382320		52
B382321		35
B382322		36
B382323		43
B382324		35
B382325		234
B382326		45
B382327		63
B382328		404
B382329		
B382330		44
B382331		16
B382332		12
B382333		17

Comments: Additional AA23 data for the following samples: B382258: 3.950, 0.452 ppm; B382260: 1.335 ppm.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05060971

Project: Dublin Gulch-1735

P.O. No.:

This report is for 60 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 26-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION


ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: 

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060971

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B382157		5.32	0.114	<0.5	8.35	203	1360	2.9	8	2.45	<0.5	10	136	20	2.92	0.01
B382158		5.84	0.499	<0.5	7.18	109	1320	2.4	66	2.28	<0.5	13	113	18	3.00	0.01
B382159		3.06	0.143	<0.5	7.13	82	1430	2.6	5	2.45	<0.5	13	163	27	3.26	0.01
B382160		3.26	0.266	0.5	7.94	245	1510	2.1	19	2.01	<0.5	10	92	93	2.62	0.01
B382161		2.06	2.12	<0.5	7.79	7450	1680	1.5	114	1.16	<0.5	35	99	32	2.19	<0.01
B382162		2.96	2.30	<0.5	7.43	6670	1660	1.4	132	1.09	<0.5	22	86	36	2.19	<0.01
B382163		5.42	0.454	<0.5	7.55	548	1540	2.8	22	2.61	<0.5	14	172	22	2.76	0.01
B382164		5.72	0.206	<0.5	7.61	277	1500	2.9	29	2.51	<0.5	10	119	28	2.79	<0.01
B382165		6.12	0.113	<0.5	7.58	271	1460	2.9	8	2.90	<0.5	12	152	31	2.87	0.01
B382166		3.76	0.027	<0.5	7.60	165	1360	2.5	<2	2.76	<0.5	12	108	21	3.25	0.01
B382167		1.58	0.119	<0.5	7.36	205	1130	2.5	4	3.43	<0.5	12	168	33	2.91	0.01
B382168		5.90	0.116	<0.5	7.71	40	1380	2.8	5	2.74	<0.5	11	122	22	2.93	0.01
B382169		0.04	0.093													
B382170		0.12	0.189	2.8	9.56	17	1080	1.2	<2	1.54	<0.5	9	9	7480	3.36	0.02
B382171		5.34	0.007	<0.5	7.58	111	1480	2.9	<2	2.91	<0.5	12	148	28	2.74	0.01
B382172		5.50	0.044	<0.5	7.33	92	1190	2.8	<2	2.63	<0.5	11	109	17	2.46	0.01
B382173		3.30	0.005	<0.5	7.67	7	1160	2.6	<2	2.62	<0.5	11	143	14	2.68	0.02
B382174		4.78	0.195	<0.5	7.00	278	1100	2.5	3	2.41	<0.5	11	137	32	2.68	0.02
B382175		3.02	0.024	<0.5	7.25	66	1300	2.6	<2	2.28	<0.5	10	161	18	2.79	0.01
B382176		1.94	<0.005	<0.5	0.14	<5	20	<0.5	<2	19.50	<0.5	1	7	2	0.10	<0.01
B382177		4.42	0.040	<0.5	7.05	67	1220	2.8	5	2.25	<0.5	9	147	13	2.25	0.01
B382178		6.56	0.122	<0.5	7.48	188	1300	2.6	12	2.52	<0.5	12	121	25	2.87	<0.01
B382179		6.32	0.057	<0.5	7.32	75	1490	2.5	<2	2.45	<0.5	13	161	15	3.25	<0.01
B382180		2.44	0.104	<0.5	7.11	194	1420	2.4	<2	2.35	<0.5	17	133	12	3.23	0.01
B382181		0.80	0.124	<0.5	7.36	217	820	2.5	2	4.03	2.6	12	158	18	2.31	0.03
B382182		1.22	0.146	<0.5	6.88	214	1060	2.3	15	2.86	1.3	13	152	17	2.57	0.01
B382183		6.58	0.160	<0.5	7.03	257	1280	2.4	12	2.18	<0.5	16	174	22	3.15	0.01
B382184		6.14	0.621	<0.5	7.49	39	1370	2.6	79	2.47	<0.5	13	126	21	3.25	0.01
B382185		4.36	0.804	<0.5	6.60	220	1240	2.2	29	2.06	<0.5	15	145	34	2.88	0.01
B382186		2.32	0.565	<0.5	6.90	178	1260	2.1	24	2.69	<0.5	17	135	17	3.39	0.01
B382187		5.68	1.000	<0.5	7.29	496	1440	2.6	30	2.38	<0.5	18	139	30	2.63	0.01
B382188		6.00	0.360	<0.5	7.42	445	1440	2.5	29	2.60	<0.5	11	125	18	2.80	0.01
B382189		0.04	0.376													
B382190		0.10	1.490	<0.5	6.78	1260	670	5.8	<2	0.02	<0.5	6	225	37	3.69	0.04
B382191		2.00	0.265	<0.5	6.75	93	1600	2.7	15	2.50	<0.5	11	111	38	2.63	0.01
B382192		6.72	0.270	<0.5	6.82	170	1510	2.7	3	2.49	<0.5	12	113	45	2.85	0.01
B382193		5.90	0.812	<0.5	7.50	454	1540	2.7	12	2.43	<0.5	11	151	54	2.90	0.01
B382194		5.48	0.320	<0.5	6.57	402	1500	2.5	18	2.57	<0.5	13	116	53	2.77	0.01
B382195		3.08	0.036	<0.5	7.69	81	1520	2.8	<2	2.36	<0.5	12	144	39	3.02	0.02
B382196		2.30	<0.005	<0.5	0.16	7	20	<0.5	<2	19.60	<0.5	1	7	3	0.14	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060971

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B382157		3.32	1.20	334	2	1.63	22	690	19	0.03	<5	488	0.34	72	10	67
B382158		3.33	1.19	352	1	1.51	29	690	18	0.07	<5	405	0.36	85	<10	78
B382159		3.22	1.21	396	1	1.59	35	710	15	0.06	<5	424	0.40	96	10	92
B382160		5.53	1.20	185	2	1.28	22	700	16	0.30	<5	448	0.32	66	100	28
B382161		5.38	1.09	108	1	0.91	33	680	17	0.50	12	388	0.32	60	200	15
B382162		5.00	1.10	104	2	0.87	30	700	19	0.50	9	367	0.31	60	180	14
B382163		3.32	1.08	329	2	1.62	18	730	22	0.06	<5	526	0.33	60	20	57
B382164		3.16	1.05	326	1	1.66	17	700	25	0.09	<5	536	0.32	58	10	62
B382165		3.27	1.11	347	2	1.77	16	730	15	0.12	<5	561	0.33	61	<10	50
B382166		2.82	1.29	435	1	1.62	20	750	13	0.03	<5	472	0.39	86	10	96
B382167		3.22	1.14	437	2	1.58	32	640	18	0.04	<5	404	0.38	91	10	79
B382168		3.07	1.15	358	1	1.77	21	700	19	0.05	<5	512	0.35	72	10	75
B382169																
B382170		3.71	1.18	495	2	3.40	9	2000	5	0.25	<5	713	0.34	176	<10	55
B382171		3.10	1.09	363	1	1.74	19	720	16	0.05	<5	552	0.34	65	<10	68
B382172		2.89	0.98	309	1	1.72	16	640	17	0.07	<5	511	0.29	51	10	57
B382173		2.36	1.08	417	<1	1.83	15	630	26	0.05	<5	515	0.29	52	<10	69
B382174		2.65	1.15	340	11	1.37	26	570	15	0.08	<5	396	0.30	67	10	63
B382175		3.08	1.13	358	1	1.53	24	630	13	0.06	<5	441	0.33	71	10	75
B382176		0.04	11.25	160	<1	0.02	<1	560	<2	0.03	<5	114	<0.01	1	<10	7
B382177		3.30	0.97	270	1	1.67	14	570	18	0.08	<5	468	0.27	51	<10	41
B382178		3.14	1.26	349	3	1.53	28	670	17	0.13	<5	445	0.34	77	10	69
B382179		3.29	1.34	371	1	1.65	31	740	12	0.06	<5	455	0.37	89	10	76
B382180		3.39	1.35	377	3	1.54	36	760	13	0.07	<5	416	0.39	97	10	87
B382181		3.23	0.74	580	2	0.70	22	700	57	0.11	38	219	0.35	87	40	322
B382182		3.05	0.88	410	2	0.99	29	690	40	0.15	22	261	0.35	85	30	198
B382183		3.09	1.32	356	2	1.47	36	730	19	0.09	<5	383	0.39	96	20	80
B382184		3.03	1.34	373	2	1.62	33	730	21	0.07	<5	450	0.40	95	10	81
B382185		3.15	1.23	308	4	1.37	38	690	13	0.10	<5	377	0.37	94	20	81
B382186		2.82	1.54	427	2	1.38	45	730	20	0.06	<5	435	0.42	106	30	94
B382187		3.29	1.29	270	4	1.49	24	740	15	0.11	<5	527	0.33	64	50	48
B382188		3.20	1.24	334	3	1.44	26	670	14	0.10	<5	492	0.33	72	40	58
B382189																
B382190		2.61	0.34	90	3	0.11	15	290	27	0.01	116	89	0.25	91	10	47
B382191		3.33	1.17	329	2	1.32	12	630	19	0.16	7	531	0.29	53	30	47
B382192		3.30	1.13	350	3	1.58	14	680	19	0.22	<5	578	0.30	55	20	49
B382193		3.50	1.17	329	2	1.51	14	670	20	0.29	<5	561	0.30	54	20	47
B382194		3.38	1.15	306	4	1.43	14	650	16	0.25	<5	514	0.29	54	40	38
B382195		3.43	1.20	318	1	1.51	19	670	15	0.20	<5	491	0.33	70	20	54
B382196		0.04	11.70	168	<1	0.02	2	500	<2	0.02	<5	120	<0.01	2	<10	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060971

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B382197		5.50	0.256	<0.5	7.43	153	1180	2.5	6	2.81	<0.5	14	156	60	2.80	0.02
B382198		4.02	0.138	<0.5	7.27	69	1200	2.3	3	2.48	<0.5	13	124	37	3.68	0.02
B382199		6.18	0.097	<0.5	7.25	91	1640	2.3	<2	2.29	<0.5	15	159	12	3.30	0.02
B382200		5.78	0.140	<0.5	7.51	316	1530	2.3	<2	2.62	<0.5	14	137	17	3.61	0.02
B382201		0.90	0.222	0.7	7.34	615	690	2.5	5	2.90	4.0	9	146	98	4.06	0.11
B382202		0.80	0.306	0.7	7.22	759	630	2.6	10	2.45	2.4	11	115	93	4.24	0.08
B382203		4.00	0.081	<0.5	7.08	272	1220	2.6	<2	2.12	1.0	7	121	27	2.04	0.04
B382204		5.94	0.119	<0.5	6.95	1825	1320	2.4	<2	2.30	1.1	10	88	43	2.03	0.05
B382205		6.76	0.245	<0.5	7.22	792	1650	2.6	10	1.93	<0.5	10	116	56	2.53	0.04
B382206		5.66	0.105	<0.5	7.26	949	1350	2.7	<2	2.02	0.8	7	79	32	2.19	0.04
B382207		7.10	0.164	0.5	7.54	531	1670	2.7	2	2.00	<0.5	6	112	43	2.65	0.02
B382208		6.00	0.122	<0.5	7.54	42	1850	3.1	<2	1.98	<0.5	8	87	33	2.75	0.03
B382209		0.04	0.110													
B382210		0.10	2.87	0.8	6.99	7	2080	3.2	<2	4.63	<0.5	22	145	94	4.98	<0.01
B382211		4.92	0.539	1.0	7.42	138	1230	2.9	23	2.47	0.9	7	130	51	2.26	0.03
B382212		4.90	0.065	<0.5	7.06	114	1520	2.8	4	1.98	<0.5	7	88	32	2.25	0.02
B382213		2.54	0.045	<0.5	6.54	110	750	2.7	<2	2.79	<0.5	7	120	16	2.16	0.02
B382214		0.74	0.052	<0.5	7.02	139	1360	2.7	<2	2.11	1.3	6	88	42	2.94	0.05
B382215		4.66	0.083	<0.5	6.93	83	1510	2.6	3	2.13	<0.5	6	112	21	2.23	0.03
B382216		1.68	<0.005	<0.5	0.17	8	30	<0.5	<2	19.90	<0.5	<1	10	2	0.12	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 5-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05060971

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B382197		3.60	0.86	388	3	1.04	33	650	33	0.61	16	307	0.30	62	30	84
B382198		3.02	1.23	335	3	1.33	31	720	21	0.82	17	393	0.37	92	30	71
B382199		2.95	1.42	406	3	1.24	35	710	24	0.05	<5	385	0.40	99	10	91
B382200		3.17	1.35	440	3	1.03	32	740	26	0.12	23	377	0.38	95	20	83
B382201		3.08	1.01	512	1	0.70	22	570	174	2.09	61	295	0.29	69	40	654
B382202		2.91	0.90	384	1	0.66	23	510	176	2.50	65	258	0.29	68	30	442
B382203		3.57	0.71	538	1	0.81	19	590	116	0.20	24	261	0.29	37	20	200
B382204		3.71	0.66	366	2	1.03	18	590	67	0.35	23	315	0.26	33	30	231
B382205		4.24	0.60	266	3	1.20	22	600	53	0.37	25	350	0.29	36	30	96
B382206		3.95	0.67	431	2	0.97	20	550	67	0.47	17	277	0.26	32	10	149
B382207		4.10	0.70	399	1	1.12	20	610	75	0.74	17	316	0.28	36	20	79
B382208		3.95	0.65	255	1	1.28	21	610	27	0.30	20	375	0.30	38	10	62
B382209																
B382210		3.28	2.87	1060	12	2.32	68	2250	28	0.29	<5	1600	0.38	164	<10	90
B382211		3.83	0.70	363	1	0.99	23	590	110	0.34	25	313	0.29	35	20	220
B382212		3.87	0.61	273	2	1.34	21	630	25	0.18	20	365	0.31	37	10	57
B382213		2.96	0.76	357	2	1.12	17	510	28	0.33	18	310	0.24	30	20	50
B382214		3.25	0.66	380	1	1.45	22	620	63	0.56	14	364	0.28	35	20	245
B382215		3.80	0.58	324	2	1.33	21	570	30	0.21	17	368	0.27	33	20	64
B382216		0.06	12.05	183	<1	0.02	5	530	2	0.01	<5	119	0.01	3	<10	7

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D[illegible] 3-AUG-2005
Account: STRGOL

CERTIFICATE VA05062472

Project: Dublin Gulch-1735

P.O. No.:

This report is for 86 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 27-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature: [signature]

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B380837		1.74	0.082		<0.5	1.64	132	90	<0.5	<2	0.11	<0.5	13	69	76	2.94
B380838		1.46	0.024		0.6	7.90	122	310	2.4	<2	0.30	<0.5	34	419	69	7.23
B380839		3.38	0.318		<0.5	1.67	80	40	0.5	4	0.13	<0.5	11	73	86	4.68
B380840		1.96	0.046		<0.5	1.97	18	80	<0.5	<2	0.04	<0.5	6	32	35	2.56
B380841		0.16	<0.005		<0.5	1.61	<5	90	<0.5	<2	0.02	<0.5	2	57	15	1.72
B380842		0.22	0.005		<0.5	2.33	<5	110	0.5	<2	0.05	<0.5	6	26	35	2.07
B380843		0.88	0.006		<0.5	1.83	<5	90	<0.5	<2	0.02	<0.5	6	62	18	1.72
B380844		1.32	0.094		<0.5	1.54	<5	60	<0.5	<2	0.02	<0.5	3	17	26	1.02
B380845		2.20	0.007		<0.5	1.52	12	70	<0.5	<2	0.04	<0.5	3	53	9	1.00
B380846		2.10	0.072		<0.5	2.36	13	230	1.0	<2	0.18	<0.5	12	28	32	2.28
B380847		0.56	0.012		<0.5	2.79	<5	230	1.0	<2	0.11	<0.5	11	78	17	1.81
B380848		0.66	<0.005		<0.5	4.18	13	320	1.1	<2	0.12	<0.5	11	32	19	2.27
B380849		0.04	<0.005													
B380850		0.12	0.434		2.8	7.99	<5	1080	1.1	<2	1.42	<0.5	10	8	6960	3.19
B380851		0.62	<0.005		<0.5	3.64	6	150	1.0	<2	0.10	<0.5	11	63	39	2.86
B380852		0.44	<0.005		<0.5	5.09	18	340	1.1	<2	0.12	<0.5	12	38	28	2.87
B380853		0.64	<0.005		<0.5	7.76	<5	610	2.1	<2	2.17	<0.5	20	77	30	4.51
B380854		0.82	<0.005		<0.5	8.11	<5	770	1.7	<2	1.68	<0.5	17	57	47	3.62
B380855		1.26	0.005		<0.5	6.01	22	390	1.8	2	1.02	<0.5	15	86	38	3.97
B380856		2.06	<0.005		<0.5	0.14	<5	20	<0.5	<2	19.75	<0.5	1	3	2	0.13
B380857		1.64	<0.005		<0.5	7.50	16	680	2.1	<2	0.52	<0.5	21	89	39	3.88
B380858		1.74	0.007		<0.5	6.74	192	540	1.8	<2	0.18	<0.5	15	55	53	4.04
B380859		2.20	<0.005		<0.5	7.09	417	520	1.9	<2	0.13	<0.5	18	120	35	4.33
B380860		1.24	0.013		1.0	5.63	463	380	1.5	<2	0.11	<0.5	13	46	64	3.22
B380861		0.46	<0.005		<0.5	7.15	44	470	1.8	<2	0.11	<0.5	14	93	30	3.39
B380862		0.44	<0.005		<0.5	6.16	180	380	1.6	2	0.12	<0.5	14	47	31	3.13
B380863		1.86	<0.005		<0.5	5.18	5	320	1.4	<2	0.17	<0.5	10	89	18	2.85
B380864		2.44	<0.005		<0.5	8.12	5	640	2.3	<2	0.21	<0.5	16	63	42	4.70
B380865		3.04	<0.005		<0.5	7.73	5	730	2.3	2	0.17	<0.5	15	103	37	3.79
B380866		2.40	<0.005		<0.5	8.22	22	690	2.0	<2	0.17	<0.5	16	62	47	3.99
B380867		0.36	4.64		<0.5	5.07	>10000	310	1.2	253	0.58	<0.5	21	111	52	6.09
B380868		2.28	0.141		<0.5	7.16	5960	800	2.5	10	1.98	<0.5	35	466	89	6.38
B380869		0.04	0.148													
B380870		0.10	1.150		<0.5	6.97	1180	640	5.9	2	0.01	<0.5	5	196	39	3.67
B380871		1.36	0.918	0.984	<0.5	7.66	9720	550	1.9	39	0.76	<0.5	48	128	54	4.42
B380872		1.36	<0.005	<0.005	<0.5	6.29	30	420	1.7	<2	0.21	<0.5	13	48	30	3.77
B380873		2.34	<0.005		<0.5	6.96	41	500	2.0	2	0.27	<0.5	15	88	32	4.12
B380874		1.72	0.043		<0.5	9.14	15	790	2.9	<2	0.15	<0.5	18	77	42	4.57
B380875		1.92	<0.005		<0.5	9.69	11	860	3.0	<2	0.19	<0.5	21	95	50	4.65
B380876		2.12	<0.005		<0.5	0.18	<5	20	<0.5	<2	19.35	<0.5	<1	2	2	0.12

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B380837		0.26	0.35	0.12	506	<1	0.02	27	370	4	0.85	5	42	0.07	20	<10
B380838		0.08	1.22	0.51	1340	1	0.04	86	940	4	1.12	13	27	0.41	162	10
B380839		0.19	0.21	0.14	1230	<1	0.01	21	420	2	1.20	<5	20	0.07	25	<10
B380840		0.18	0.34	0.11	604	1	0.01	16	160	<2	0.40	<5	69	0.09	29	<10
B380841		0.02	0.44	0.10	435	1	0.01	8	60	<2	0.07	6	30	0.06	16	10
B380842		0.05	0.60	0.13	513	<1	0.01	16	150	4	0.50	7	75	0.13	27	<10
B380843		0.06	0.45	0.09	269	1	0.01	17	100	4	0.68	6	49	0.10	18	<10
B380844		0.21	0.31	0.07	233	<1	0.01	10	100	5	0.21	<5	47	0.05	12	<10
B380845		0.01	0.29	0.08	230	<1	0.01	11	110	2	0.08	<5	16	0.07	14	<10
B380846		0.01	0.85	0.32	272	<1	0.06	34	200	3	0.49	<5	33	0.13	28	<10
B380847		0.01	0.80	0.22	338	1	0.02	31	230	7	0.48	5	18	0.17	32	10
B380848		0.01	1.11	0.32	380	1	0.04	26	230	11	0.34	<5	24	0.20	43	<10
B380849																
B380850		0.03	3.30	1.06	471	4	3.15	9	1880	7	0.22	<5	647	0.32	167	<10
B380851		0.02	0.62	0.37	482	1	0.03	25	230	8	0.35	<5	52	0.17	33	<10
B380852		0.01	1.29	0.40	427	1	0.07	28	280	10	0.40	<5	53	0.23	47	<10
B380853		0.02	2.74	1.49	943	<1	0.12	30	290	10	0.26	<5	201	0.33	81	10
B380854		0.01	3.00	1.18	775	3	0.15	44	310	5	0.26	<5	176	0.32	101	<10
B380855		0.04	1.72	0.96	578	1	0.07	29	300	5	0.87	<5	173	0.28	68	<10
B380856		<0.01	0.04	11.20	146	<1	0.02	<1	480	<2	<0.01	<5	110	<0.01	2	<10
B380857		0.01	2.63	0.90	435	<1	0.18	43	360	8	0.48	<5	99	0.35	85	<10
B380858		0.01	2.28	0.94	275	1	0.12	31	340	9	0.58	<5	46	0.31	72	<10
B380859		0.01	2.18	0.74	492	1	0.09	36	330	8	0.50	<5	48	0.30	74	10
B380860		0.02	1.56	0.41	543	1	0.05	32	330	12	0.45	<5	47	0.24	65	10
B380861		0.02	1.99	0.44	484	<1	0.11	36	310	17	0.37	<5	60	0.35	64	<10
B380862		0.02	1.71	0.43	402	1	0.09	33	280	19	0.40	<5	58	0.30	61	<10
B380863		0.01	1.33	0.61	235	<1	0.68	23	220	20	0.31	<5	51	0.24	42	<10
B380864		0.01	2.66	1.11	491	1	0.34	41	320	25	0.65	<5	65	0.36	85	<10
B380865		0.01	2.82	0.95	293	1	0.39	37	330	24	0.60	<5	75	0.35	86	<10
B380866		0.01	3.30	1.05	253	<1	0.43	36	300	16	0.82	<5	71	0.36	85	<10
B380867		0.02	1.51	0.84	296	<1	0.73	29	190	8	2.34	51	86	0.17	44	<10
B380868		0.02	2.17	3.01	720	1	0.10	86	770	10	0.75	9	179	0.35	117	10
B380869																
B380870		0.05	2.67	0.34	82	2	0.11	19	300	28	0.01	110	90	0.24	84	10
B380871		0.02	2.47	1.21	371	<1	0.33	42	320	10	0.86	12	113	0.31	79	<10
B380872		0.01	1.83	0.75	441	<1	0.13	37	230	12	0.59	<5	61	0.27	58	<10
B380873		0.04	2.05	0.87	491	1	0.22	36	300	18	0.76	<5	52	0.31	66	<10
B380874		0.03	3.23	0.95	299	<1	0.45	47	350	24	0.48	<5	74	0.44	105	<10
B380875		0.02	3.40	1.00	359	1	0.41	46	390	27	0.65	<5	92	0.44	109	<10
B380876		<0.01	0.05	11.35	147	<1	0.01	4	500	<2	<0.01	<5	109	0.01	3	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B380837		36
B380838		207
B380839		71
B380840		48
B380841		30
B380842		53
B380843		31
B380844		27
B380845		33
B380846		81
B380847		86
B380848		70
B380849		
B380850		47
B380851		70
B380852		78
B380853		104
B380854		74
B380855		94
B380856		8
B380857		90
B380858		69
B380859		95
B380860		128
B380861		114
B380862		90
B380863		90
B380864		92
B380865		80
B380866		59
B380867		34
B380868		113
B380869		
B380870		44
B380871		36
B380872		88
B380873		89
B380874		107
B380875		93
B380876		8

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B380877		2.18	<0.005		<0.5	8.47	<5	610	2.6	<2	0.37	<0.5	17	88	37	4.48
B380878		1.40	<0.005		<0.5	8.47	14	690	2.5	<2	0.37	<0.5	15	63	34	3.75
B380879		1.24	<0.005		<0.5	7.37	<5	450	2.0	<2	0.62	<0.5	12	79	28	4.09
B380880		1.88	<0.005		<0.5	6.31	7	350	1.8	<2	0.44	<0.5	9	40	22	3.72
B380881		0.42	<0.005		<0.5	7.58	9	520	1.9	<2	0.30	<0.5	11	70	25	3.29
B380882		0.32	<0.005		<0.5	8.19	7	620	2.1	<2	0.40	<0.5	16	58	33	3.67
B380883		0.58	<0.005		<0.5	7.71	13	460	1.9	<2	0.86	<0.5	10	82	15	2.98
B380884		2.70	0.011		<0.5	5.26	7	320	1.2	<2	0.55	<0.5	9	38	26	2.98
B380885		3.72	<0.005		<0.5	7.40	8	560	1.8	<2	0.37	<0.5	11	81	25	3.39
B380886		3.54	<0.005		<0.5	7.89	<5	650	2.1	<2	0.30	<0.5	14	61	39	4.27
B380887		3.02	<0.005		<0.5	7.45	15	490	1.9	<2	0.35	<0.5	12	76	30	3.59
B380888		2.72	0.013		<0.5	6.43	8	390	1.6	<2	0.36	<0.5	11	45	23	3.19
B380889		0.04	0.011													
B380890		0.10	4.56		8.8	7.99	12	460	0.9	<2	2.76	1.2	17	20	128	4.21
B380891		2.92	0.008		<0.5	5.17	5	260	1.0	<2	0.56	<0.5	9	76	15	2.81
B380892		2.86	0.008		<0.5	7.91	7	620	2.0	<2	0.54	<0.5	16	58	39	3.57
B380893		3.34	0.009		<0.5	7.45	12	590	1.9	<2	0.46	<0.5	12	94	32	3.64
B380894		2.70	0.010		<0.5	6.06	54	390	1.2	<2	0.48	<0.5	10	53	27	2.75
B380895		2.50	<0.005		<0.5	8.80	5	740	2.7	<2	0.23	<0.5	18	103	44	4.27
B380896		1.90	<0.005		<0.5	0.16	<5	20	<0.5	<2	19.35	<0.5	1	2	2	0.13
B380897		3.06	<0.005		<0.5	5.92	<5	350	1.5	<2	0.76	<0.5	10	86	23	2.82
B380898		3.10	<0.005		<0.5	7.55	<5	520	2.1	<2	0.72	<0.5	14	57	33	3.58
B380899		3.20	<0.005		<0.5	6.47	12	410	1.5	<2	0.68	<0.5	13	109	27	2.98
B380900		3.14	<0.005		<0.5	8.28	14	690	2.2	<2	0.48	<0.5	15	74	51	3.55
B380901		1.84	<0.005		<0.5	8.05	16	660	2.2	<2	0.30	<0.5	16	108	35	3.75
B380902		1.50	<0.005		<0.5	8.77	15	670	2.3	<2	0.35	<0.5	16	73	35	3.91
B380903		2.72	0.011		<0.5	5.77	19	390	1.3	<2	0.62	<0.5	10	103	27	2.85
B380904		2.50	<0.005		<0.5	8.02	15	620	2.1	<2	0.43	<0.5	14	67	31	3.39
B380905		2.68	<0.005		<0.5	9.32	10	740	2.4	<2	0.59	<0.5	19	126	41	4.34
B380906		3.48	<0.005		<0.5	8.62	10	770	2.4	<2	0.33	<0.5	19	73	43	4.16
B380907		2.38	0.006		<0.5	7.42	<5	620	2.0	2	0.34	<0.5	12	99	31	3.65
B380908		2.64	<0.005		<0.5	8.45	7	670	2.2	<2	0.27	<0.5	17	72	39	3.57
B380909		0.04	<0.005													
B380910		0.10	0.092		<0.5	7.23	110	590	2.6	<2	0.52	<0.5	59	1215	403	8.59
B380911		2.80	<0.005		<0.5	9.81	9	890	3.0	<2	0.16	<0.5	20	121	52	4.82
B380912		3.10	<0.005		<0.5	9.98	10	850	2.6	<2	0.27	<0.5	21	89	48	5.00
B380913		3.64	<0.005		<0.5	5.77	16	390	1.1	<2	0.59	<0.5	10	91	18	2.84
B380914		1.88	0.112		<0.5	3.77	56	180	0.7	3	0.87	<0.5	12	34	78	3.46
B380915		0.94	<0.005		<0.5	8.52	<5	680	2.5	<2	0.19	<0.5	18	122	39	4.45
B380916		3.22	<0.005		<0.5	0.16	<5	20	<0.5	<2	21.3	<0.5	3	4	2	0.14

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B380877		0.02	2.47	0.97	547	<1	0.24	42	330	31	0.47	<5	80	0.35	85	<10
B380878		0.02	2.57	0.81	502	<1	0.24	40	310	31	0.43	<5	84	0.38	89	<10
B380879		0.06	2.13	1.09	547	<1	0.13	33	270	18	0.54	<5	147	0.29	66	<10
B380880		0.04	1.53	0.90	321	<1	0.44	26	240	18	0.47	<5	79	0.26	52	<10
B380881		0.01	2.13	0.74	309	<1	1.08	36	310	26	0.53	<5	99	0.30	69	<10
B380882		0.02	2.56	0.82	328	<1	1.15	36	360	30	0.69	<5	113	0.35	82	<10
B380883		0.02	2.08	0.77	432	<1	0.95	32	280	16	0.26	<5	101	0.33	71	<10
B380884		0.01	1.23	0.72	317	<1	0.83	23	220	17	0.47	<5	87	0.24	45	<10
B380885		0.01	2.13	0.85	325	<1	0.93	30	280	21	0.49	<5	111	0.31	68	<10
B380886		0.01	2.60	1.00	233	<1	0.67	36	300	21	0.70	<5	102	0.37	82	<10
B380887		0.02	1.98	0.88	364	<1	0.32	30	300	21	0.45	<5	89	0.32	68	<10
B380888		0.02	1.62	0.78	381	<1	0.52	28	250	14	0.27	<5	75	0.29	54	<10
B380889																
B380890		0.02	2.30	1.32	938	12	1.69	13	910	28	0.66	<5	411	0.37	144	<10
B380891		0.01	1.03	0.72	518	<1	1.12	23	200	16	0.16	<5	81	0.22	39	<10
B380892		0.01	2.49	0.91	366	<1	0.96	33	300	23	0.53	<5	102	0.35	79	<10
B380893		0.01	2.47	0.95	303	<1	0.81	33	270	21	0.46	<5	81	0.34	74	<10
B380894		0.01	1.61	0.69	281	<1	0.96	33	220	15	0.34	<5	85	0.25	50	<10
B380895		0.01	3.31	1.05	256	1	0.43	45	350	30	0.69	<5	81	0.39	101	<10
B380896		<0.01	0.04	11.40	145	<1	0.02	4	470	3	<0.01	<5	117	0.01	3	<10
B380897		0.01	1.61	0.89	324	1	0.27	25	240	19	0.38	<5	114	0.26	55	<10
B380898		0.01	2.50	0.94	250	<1	0.32	33	280	20	0.60	<5	106	0.32	81	<10
B380899		0.01	1.80	0.83	305	1	0.62	26	250	18	0.42	<5	85	0.26	63	<10
B380900		0.01	3.07	0.94	234	1	0.65	37	320	18	0.73	<5	96	0.36	94	<10
B380901		0.01	2.94	0.94	218	2	0.66	32	290	24	0.69	<5	81	0.38	93	<10
B380902		0.01	2.92	0.96	236	1	0.69	36	300	22	0.68	<5	86	0.39	93	<10
B380903		0.01	1.56	0.69	289	<1	0.84	22	230	21	0.51	<5	79	0.26	53	<10
B380904		0.01	2.62	0.85	232	1	0.66	25	270	16	0.46	<5	100	0.37	85	<10
B380905		0.01	3.05	1.04	315	1	0.72	39	440	31	0.79	<5	123	0.45	108	<10
B380906		0.01	3.30	0.95	221	1	0.77	37	290	21	1.06	<5	104	0.39	99	<10
B380907		0.01	2.42	0.85	272	<1	0.71	31	330	18	0.50	<5	100	0.32	79	<10
B380908		0.01	2.85	0.85	214	1	0.64	36	270	26	0.66	<5	96	0.37	92	<10
B380909																
B380910		0.03	2.23	0.59	384	9	0.12	480	350	160	0.03	14	53	0.22	90	30
B380911		0.01	3.82	1.01	177	1	0.64	45	370	41	1.13	<5	115	0.48	124	<10
B380912		0.01	3.59	1.22	275	1	0.73	44	350	24	0.77	<5	109	0.48	117	<10
B380913		<0.01	1.48	0.80	360	1	1.11	18	240	12	0.34	<5	93	0.28	50	<10
B380914		0.01	0.91	0.59	211	<1	0.46	21	330	9	1.51	<5	87	0.15	26	<10
B380915		<0.01	3.11	1.07	205	<1	0.49	35	300	19	0.55	<5	90	0.44	104	10
B380916		<0.01	0.04	11.95	158	<1	0.01	4	560	<2	0.01	<5	114	<0.01	2	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B380877		110
B380878		101
B380879		107
B380880		95
B380881		91
B380882		81
B380883		68
B380884		59
B380885		72
B380886		90
B380887		92
B380888		78
B380889		
B380890		99
B380891		75
B380892		66
B380893		74
B380894		53
B380895		91
B380896		8
B380897		60
B380898		75
B380899		55
B380900		60
B380901		77
B380902		78
B380903		52
B380904		68
B380905		90
B380906		71
B380907		77
B380908		72
B380909		
B380910		608
B380911		90
B380912		100
B380913		54
B380914		27
B380915		97
B380916		8

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B380917		3.28	<0.005		<0.5	10.40	6	890	2.9	<2	0.25	<0.5	22	118	39	4.56
B380918		2.94	<0.005		<0.5	9.87	8	810	2.7	<2	0.29	<0.5	23	91	52	4.99
B380919		3.18	<0.005		<0.5	9.73	<5	840	2.8	<2	0.24	<0.5	21	125	47	4.83
B380920		3.00	0.006		<0.5	6.42	8	430	1.6	<2	0.85	<0.5	11	48	22	2.83
B380921		1.38	<0.005		<0.5	5.71	16	350	1.1	<2	1.22	<0.5	13	90	16	2.77
B380922		1.58	<0.005		<0.5	6.37	16	430	1.2	<2	0.78	<0.5	11	53	20	2.61

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method / Analyte / Units / LOR	Hg-CV41 Hg ppm 0.01	ME-ICP61 K % 0.01	ME-ICP61 Mg % 0.01	ME-ICP61 Mn ppm 5	ME-ICP61 Mo ppm 1	ME-ICP61 Na % 0.01	ME-ICP61 Ni ppm 1	ME-ICP61 P ppm 10	ME-ICP61 Pb ppm 2	ME-ICP61 S % 0.01	ME-ICP61 Sb ppm 5	ME-ICP61 Sr ppm 1	ME-ICP61 Ti % 0.01	ME-ICP61 V ppm 1	ME-ICP61 W ppm 10
B380917		0.05	3.94	1.15	229	1	0.53	39	340	30	0.63	<5	103	0.53	127	10
B380918		0.03	3.63	1.29	298	2	0.31	47	370	35	0.87	<5	73	0.47	125	<10
B380919		0.03	3.69	1.19	265	14	0.40	47	350	45	0.95	<5	77	0.46	119	<10
B380920		0.02	1.94	0.78	376	<1	0.56	19	230	20	0.41	<5	65	0.25	59	<10
B380921		0.01	1.51	0.82	512	<1	0.95	20	210	17	0.24	<5	91	0.26	47	<10
B380922		0.01	1.80	0.75	334	<1	0.91	23	200	22	0.27	<5	88	0.29	55	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062472

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 Zn ppm 2
B380917		91
B380918		94
B380919		91
B380920		53
B380921		48
B380922		49

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 5-AUG-2005
Account: STRGOL

CERTIFICATE VA05062473

Project: Dublin Gulch-1735

P.O. No.:

This report is for 82 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 27-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380923		1.94	<0.005	<0.5	6.71	51	1390	2.1	<2	2.65	<0.5	11	128	37	3.09	0.01
B380924		1.42	<0.005	<0.5	6.22	28	1100	2.1	<2	2.50	<0.5	7	128	12	2.80	<0.01
B380925		1.34	<0.005	<0.5	7.86	33	1490	3.0	<2	2.22	<0.5	6	87	6	2.48	<0.01
B380926		0.88	<0.005	<0.5	5.95	21	1060	2.3	<2	1.44	<0.5	5	127	6	2.12	<0.01
B380927		1.48	0.014	<0.5	4.86	42	390	1.0	<2	1.36	<0.5	12	109	107	3.73	0.02
B380928		1.94	<0.005	<0.5	2.48	29	100	0.5	4	0.73	<0.5	5	157	197	2.78	0.04
B380929		0.04	<0.005													
B380930		0.12	3.02	0.7	6.34	19	1920	3.0	<2	4.29	<0.5	20	130	95	4.59	0.01
B380931		1.48	0.006	<0.5	7.00	36	210	1.3	<2	0.21	<0.5	17	109	93	4.57	0.01
B380932		2.12	<0.005	<0.5	4.09	64	220	0.8	<2	1.30	<0.5	12	159	130	3.97	0.03
B380933		3.74	0.005	<0.5	6.08	166	250	1.1	<2	0.31	<0.5	24	111	98	5.59	0.02
B380934		4.10	0.019	<0.5	5.74	455	350	1.3	<2	1.41	0.6	10	156	29	3.05	0.05
B380935		4.10	<0.005	<0.5	3.73	69	170	0.7	<2	0.44	<0.5	5	105	10	2.30	0.02
B380936		2.70	<0.005	<0.5	0.13	10	10	<0.5	<2	18.05	<0.5	<1	7	2	0.11	0.01
B380937		3.44	<0.005	<0.5	7.78	25	560	2.1	<2	0.63	<0.5	13	114	18	4.35	0.02
B380938		4.88	<0.005	<0.5	6.38	5	310	1.3	<2	1.90	<0.5	15	118	37	4.60	0.03
B380939		4.28	<0.005	<0.5	6.31	8	460	1.6	<2	0.51	<0.5	13	110	37	3.70	0.01
B380940		5.62	<0.005	<0.5	2.79	17	170	0.5	2	0.71	<0.5	10	161	94	2.37	0.02
B380941		3.08	<0.005	<0.5	6.57	13	480	1.6	<2	0.28	<0.5	15	109	45	3.76	0.01
B380942		2.80	<0.005	<0.5	7.06	12	540	1.8	<2	0.30	<0.5	17	132	34	4.01	<0.01
B380943		5.62	<0.005	<0.5	2.93	<5	130	0.5	<2	0.78	<0.5	7	91	17	2.07	0.01
B380944		5.40	<0.005	<0.5	2.61	<5	120	<0.5	<2	0.62	<0.5	6	125	12	1.46	0.01
B380945		5.32	<0.005	<0.5	2.89	<5	180	0.5	<2	0.68	<0.5	5	85	15	1.72	<0.01
B380946		3.92	<0.005	<0.5	2.36	<5	100	<0.5	<2	1.15	<0.5	6	142	10	1.96	<0.01
B380947		2.14	<0.005	<0.5	6.33	<5	510	1.5	<2	0.39	<0.5	14	108	29	3.02	<0.01
B380948		5.38	<0.005	<0.5	7.50	<5	540	2.0	<2	0.89	<0.5	15	144	39	4.15	0.01
B380949		0.04	<0.005													
B380950		0.12	2.54	<0.5	7.27	2100	710	11.2	<2	0.01	<0.5	<1	138	98	3.38	0.08
B380951		6.48	<0.005	<0.5	6.78	15	470	1.7	<2	1.24	<0.5	12	98	19	3.35	<0.01
B380952		1.16	<0.005	<0.5	3.13	67	160	0.9	<2	2.17	<0.5	5	155	16	2.44	0.01
B380953		3.88	<0.005	<0.5	5.95	9	280	1.4	<2	1.29	<0.5	18	95	66	5.21	0.07
B380954		6.46	<0.005	<0.5	6.58	<5	310	1.4	<2	3.68	1.0	14	103	38	4.11	0.03
B380955		6.14	<0.005	<0.5	5.95	<5	290	1.2	<2	1.87	<0.5	16	88	47	3.43	0.01
B380956		2.72	<0.005	<0.5	0.16	<5	20	<0.5	<2	18.95	<0.5	<1	8	2	0.13	<0.01
B380957		5.54	0.005	<0.5	6.24	118	250	1.2	<2	1.74	<0.5	25	103	92	5.58	0.01
B380958		1.56	0.029	<0.5	6.65	155	200	1.5	<2	0.81	<0.5	24	107	93	4.45	0.02
B380959		3.44	0.010	<0.5	5.63	87	160	1.0	<2	2.44	<0.5	21	89	86	5.64	0.01
B380960		5.42	<0.005	<0.5	6.42	10	130	1.0	<2	2.31	<0.5	29	120	106	5.91	0.01
B380961		2.76	<0.005	<0.5	5.36	10	350	0.9	<2	1.49	<0.5	21	111	67	4.86	0.01
B380962		2.94	<0.005	<0.5	5.03	13	300	0.9	<2	1.67	<0.5	19	129	87	4.72	0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380923		2.35	1.34	457	1	1.44	40	580	16	0.04	<5	496	0.33	62	<10	59
B380924		2.32	1.01	526	1	1.38	25	480	15	0.02	<5	414	0.26	46	20	44
B380925		3.58	0.92	353	1	1.82	17	590	28	0.01	5	521	0.28	43	<10	62
B380926		2.28	0.66	336	1	1.36	16	460	20	0.01	<5	346	0.23	39	<10	42
B380927		0.95	0.95	624	<1	0.48	33	300	11	0.15	11	132	0.36	101	10	42
B380928		0.45	0.56	482	<1	0.01	13	130	10	0.47	10	66	0.17	34	10	14
B380929																
B380930		3.09	2.62	949	12	2.12	58	2080	29	0.27	5	1545	0.33	150	10	87
B380931		0.63	0.38	499	1	0.03	43	340	18	0.05	36	38	0.61	192	<10	78
B380932		0.58	0.87	666	2	0.27	29	290	12	0.42	14	129	0.33	89	<10	40
B380933		0.77	0.60	924	1	0.02	50	320	18	0.31	22	31	0.53	170	10	108
B380934		2.50	0.90	1370	<1	0.04	20	240	41	0.19	16	63	0.30	72	10	164
B380935		0.78	0.36	315	1	0.01	17	150	19	0.02	15	70	0.23	46	<10	39
B380936		0.04	10.40	149	<1	0.01	1	420	<2	0.01	<5	108	0.01	1	<10	6
B380937		3.46	1.09	525	1	0.05	32	340	11	0.07	17	53	0.34	103	<10	46
B380938		2.01	1.29	725	<1	0.03	37	250	7	0.13	8	69	0.32	76	<10	53
B380939		2.31	0.92	441	<1	0.04	32	340	6	0.10	11	94	0.35	81	<10	54
B380940		0.65	0.56	257	1	0.01	14	160	6	0.52	19	62	0.19	37	<10	17
B380941		2.49	0.88	377	<1	0.05	35	290	5	0.04	16	97	0.34	86	<10	53
B380942		2.82	0.95	418	<1	0.05	37	270	4	0.03	13	101	0.41	95	<10	51
B380943		0.46	0.57	340	<1	0.01	13	170	7	0.04	<5	83	0.20	36	<10	20
B380944		0.40	0.41	273	<1	0.01	12	130	5	0.02	<5	56	0.19	35	<10	18
B380945		0.69	0.48	431	<1	0.02	12	120	7	0.02	<5	38	0.21	40	<10	21
B380946		0.43	0.70	561	1	0.01	11	120	6	0.02	<5	36	0.18	32	<10	26
B380947		2.46	0.77	444	<1	0.04	28	310	7	0.02	<5	62	0.43	86	<10	53
B380948		3.07	1.19	469	1	0.06	36	340	4	0.13	5	93	0.39	99	<10	69
B380949																
B380950		3.05	0.37	68	3	0.09	10	310	29	0.02	140	132	0.19	101	10	16
B380951		2.65	1.14	389	1	0.05	32	310	3	0.16	5	80	0.40	88	<10	36
B380952		0.87	0.97	481	1	0.02	15	130	9	0.15	11	94	0.20	42	10	16
B380953		1.59	1.26	677	<1	0.05	40	250	8	0.80	15	108	0.31	81	<10	48
B380954		1.82	1.96	1265	1	0.04	37	330	44	0.44	13	158	0.36	92	<10	200
B380955		1.63	1.23	564	1	0.04	37	260	7	0.44	11	89	0.40	102	<10	61
B380956		0.04	11.20	158	<1	0.01	<1	520	3	0.02	<5	110	0.01	2	<10	7
B380957		1.06	1.55	837	1	0.03	53	340	7	0.54	11	74	0.55	182	<10	66
B380958		1.52	1.17	516	1	0.04	52	350	22	0.38	6	108	0.57	177	10	85
B380959		1.36	1.90	873	<1	0.04	47	310	13	0.06	30	64	0.49	164	<10	64
B380960		1.29	1.92	760	1	0.03	57	360	17	0.10	33	52	0.58	197	10	74
B380961		1.83	1.56	612	1	0.03	47	280	11	0.13	<5	43	0.48	154	<10	57
B380962		1.68	1.58	667	1	0.04	43	270	17	0.13	<5	46	0.44	144	<10	67

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B380963		4.80	<0.005	<0.5	6.09	9	480	1.3	<2	0.72	<0.5	17	119	49	4.32	0.01
B380964		5.64	<0.005	<0.5	5.87	<5	420	1.3	<2	0.65	<0.5	11	117	33	3.52	<0.01
B380965		4.78	<0.005	<0.5	5.13	<5	380	1.2	<2	0.92	<0.5	12	83	34	3.09	<0.01
B380966		4.04	0.006	<0.5	5.63	13	400	1.3	<2	1.10	<0.5	12	133	38	3.59	<0.01
B380967		5.82	<0.005	<0.5	4.34	<5	460	0.9	<2	15.65	<0.5	6	56	26	2.29	<0.01
B380968		2.76	<0.005	<0.5	3.01	<5	380	0.8	<2	3.58	<0.5	4	97	15	1.90	<0.01
B380969		0.04	<0.005													
B380970		0.12	1.430	<0.5	7.02	1310	700	5.6	<2	0.02	<0.5	4	219	40	3.87	0.05
B380971		1.70	<0.005	<0.5	7.72	<5	610	1.9	<2	0.66	<0.5	15	103	48	4.95	<0.01
B380972		5.22	<0.005	<0.5	4.61	29	420	1.2	<2	2.23	<0.5	10	158	47	3.45	0.01
B380973		3.84	<0.005	<0.5	4.42	<5	440	1.1	<2	1.67	<0.5	10	164	40	3.30	0.01
B380974		2.00	<0.005	<0.5	4.22	6	360	1.0	<2	0.89	<0.5	8	105	28	2.82	<0.01
B380975		3.16	<0.005	<0.5	6.07	6	490	1.4	<2	0.70	<0.5	8	122	24	2.92	<0.01
B380976		2.74	<0.005	<0.5	0.12	<5	20	<0.5	<2	19.10	<0.5	<1	6	2	0.11	<0.01
B380977		1.72	<0.005	<0.5	4.57	<5	300	0.9	<2	0.53	<0.5	5	122	13	2.09	<0.01
B380978		3.58	<0.005	<0.5	6.87	<5	540	1.8	<2	0.37	<0.5	10	98	31	3.66	<0.01
B380979		1.82	<0.005	<0.5	5.63	7	430	1.4	<2	1.08	<0.5	8	126	22	2.72	<0.01
B380980		2.50	<0.005	<0.5	5.81	8	440	1.4	<2	0.45	<0.5	9	89	26	2.99	<0.01
B380981		0.72	0.038	<0.5	8.29	14	620	2.1	<2	0.68	<0.5	12	113	152	4.04	0.01
B380982		0.52	<0.005	<0.5	8.15	10	540	1.9	<2	0.34	<0.5	15	105	47	4.50	<0.01
B380983		4.00	0.011	<0.5	3.82	65	220	0.9	<2	0.41	<0.5	5	123	18	1.74	<0.01
B380984		4.54	<0.005	<0.5	3.83	<5	200	0.7	<2	0.46	<0.5	6	80	11	1.57	<0.01
B380985		3.06	<0.005	<0.5	2.88	7	120	0.5	<2	0.31	<0.5	4	112	17	1.16	<0.01
B380986		1.14	<0.005	<0.5	2.80	<5	160	0.5	<2	0.20	<0.5	3	69	21	0.95	<0.01
B380987		2.60	0.007	<0.5	2.30	76	80	<0.5	<2	0.19	<0.5	3	131	16	1.09	<0.01
B380988		2.70	<0.005	<0.5	1.84	50	60	<0.5	<2	0.28	<0.5	3	91	17	0.80	<0.01
B380989		0.06	0.005													
B380990		0.12	0.085	<0.5	7.09	118	580	2.5	<2	0.53	<0.5	58	1185	404	8.70	0.03
B380991		Not Recvd														
B380992		Not Recvd														
B380993		Not Recvd														
B380994		Not Recvd														
B380995		4.04	0.168	1.1	8.88	1255	780	2.3	2	0.31	1.3	14	137	84	3.75	0.02
B380996		1.00	<0.005	<0.5	0.16	<5	20	<0.5	<2	18.75	<0.5	<1	8	3	0.13	0.01
B380997		1.70	0.007	0.5	7.06	5	590	1.9	<2	0.40	0.6	10	142	45	3.58	0.01
B380998		2.80	0.637	15.6	7.10	1030	620	2.0	28	0.49	1.5	12	98	84	4.56	0.24
B380999		4.38	<0.005	<0.5	8.69	<5	750	2.6	<2	0.51	<0.5	17	142	46	4.75	<0.01
B381000		3.40	<0.005	<0.5	9.63	<5	930	2.2	<2	0.62	<0.5	17	132	54	4.45	<0.01
B381001		0.92	<0.005	<0.5	10.00	<5	980	3.2	2	0.53	<0.5	20	130	61	5.47	<0.01
B381002		0.92	<0.005	<0.5	9.78	<5	940	2.8	2	0.42	<0.5	19	115	65	5.41	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380963		2.40	1.16	548	<1	0.07	36	300	20	0.37	<5	47	0.42	104	<10	64
B380964		2.31	0.97	494	<1	0.08	29	300	14	0.12	<5	54	0.36	74	10	62
B380965		2.09	0.94	597	<1	0.07	27	240	18	0.12	<5	63	0.31	66	<10	55
B380966		2.28	1.08	599	1	0.09	30	300	8	0.45	<5	72	0.31	67	10	56
B380967		2.53	0.81	487	1	0.08	18	340	12	0.64	<5	1240	0.22	44	<10	38
B380968		1.84	0.87	384	<1	0.04	15	230	9	0.48	<5	270	0.15	33	<10	23
B380969																
B380970		2.75	0.36	89	3	0.11	18	320	27	0.02	113	90	0.22	93	10	47
B380971		3.42	1.63	516	<1	0.31	44	710	16	0.73	<5	62	0.37	99	<10	88
B380972		2.14	1.30	619	2	0.18	29	420	10	1.20	<5	172	0.20	75	<10	40
B380973		2.19	1.20	590	2	0.21	31	460	10	1.15	<5	178	0.19	73	10	59
B380974		1.72	1.00	368	1	0.39	24	310	6	0.36	<5	115	0.17	47	<10	44
B380975		2.20	0.85	248	1	0.57	24	320	14	0.44	<5	127	0.25	53	<10	52
B380976		0.03	11.05	151	<1	0.01	3	470	3	0.01	<5	108	0.01	2	<10	7
B380977		1.43	0.64	217	1	0.69	16	230	16	0.20	<5	94	0.19	37	<10	42
B380978		2.49	0.96	294	1	0.44	29	320	17	0.34	<5	92	0.31	72	<10	71
B380979		2.13	0.81	276	1	0.43	23	260	17	0.31	<5	108	0.25	55	<10	56
B380980		2.15	0.79	323	1	0.32	26	280	16	0.40	<5	106	0.26	58	<10	55
B380981		3.26	1.20	284	4	0.40	39	390	33	0.49	<5	140	0.37	104	<10	73
B380982		2.83	1.11	264	2	0.39	39	310	23	0.61	<5	99	0.36	81	10	90
B380983		1.09	0.46	138	1	0.25	13	180	7	0.27	7	71	0.14	32	<10	30
B380984		0.95	0.40	137	1	0.58	12	190	9	0.15	10	75	0.17	28	<10	26
B380985		0.62	0.24	106	1	0.52	9	140	6	0.17	<5	50	0.12	20	10	10
B380986		0.76	0.20	101	<1	0.22	4	170	13	0.14	7	34	0.12	20	<10	22
B380987		0.39	0.16	88	1	0.61	7	130	5	0.23	<5	30	0.10	16	<10	9
B380988		0.30	0.16	59	<1	0.47	6	120	6	0.17	<5	36	0.08	13	<10	7
B380989																
B380990		2.23	0.60	380	8	0.12	493	350	154	0.02	11	50	0.22	93	30	618
B380991																
B380992																
B380993																
B380994																
B380995		3.82	0.86	347	1	0.14	41	360	207	0.86	90	100	0.40	113	10	204
B380996		0.04	10.95	135	<1	0.02	3	560	5	0.02	<5	113	0.01	2	<10	7
B380997		2.60	0.88	203	1	0.15	35	280	92	0.79	23	129	0.31	80	<10	126
B380998		2.96	0.89	278	1	0.12	34	330	1440	2.01	40	108	0.27	75	10	219
B380999		3.05	1.26	364	2	0.30	41	390	22	0.60	8	112	0.42	110	<10	85
B381000		3.71	1.12	297	2	0.31	44	360	23	0.98	<5	124	0.42	114	<10	76
B381001		4.09	1.16	299	1	0.25	49	360	31	1.56	<5	130	0.41	126	<10	97
B381002		3.88	1.10	261	2	0.25	51	320	32	1.56	<5	119	0.40	121	<10	107

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01	Hg-CV41 Hg ppm 0.01
B381003		4.40	<0.005	<0.5	8.58	<5	830	2.4	2	0.32	<0.5	17	141	52	5.08	<0.01
B381004		3.78	<0.005	<0.5	8.66	<5	750	2.4	<2	0.28	<0.5	17	122	44	4.72	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 6-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062473

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B381003		3.46	1.36	532	3	0.24	46	400	27	1.04	<5	79	0.43	128	<10	98
B381004		2.96	1.07	249	1	0.55	40	330	28	0.92	<5	98	0.41	103	<10	86

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized D 3-AUG-2005
Account: STRGOL

CERTIFICATE VA05062470

Project: Dublin Gulch-1735

P.O. No.:

This report is for 53 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 27-JUL-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method / Analyte / Units / LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B382334		3.14	0.526		<0.5	7.01	102	1350	2.8	9	2.11	<0.5	8	104	98	2.65
B382335		2.60	0.035		<0.5	7.35	39	1330	2.9	<2	2.38	<0.5	6	146	50	2.76
B382336		2.30	<0.005	<0.005	<0.5	0.13	<5	20	<0.5	<2	18.30	<0.5	<1	12	2	0.12
B382337		2.10	0.062	0.088	<0.5	6.60	47	1350	2.7	4	2.41	<0.5	8	142	65	2.56
B382338		3.82	0.037		<0.5	7.56	75	1410	2.8	2	2.37	<0.5	8	100	56	2.51
B382339		6.68	0.083		<0.5	7.33	138	1510	3.0	<2	2.31	<0.5	9	100	81	2.58
B382340		3.02	0.177		<0.5	7.11	146	1320	2.5	13	1.60	<0.5	7	125	65	1.99
B382341		1.38	1.790		<0.5	6.97	347	1330	2.6	229	1.89	<0.5	8	106	89	2.28
B382342		1.58	0.129		<0.5	7.27	147	1470	3.0	2	2.12	<0.5	8	150	90	2.49
B382343		6.34	0.104		<0.5	7.25	27	1250	2.8	2	2.44	<0.5	8	108	64	2.69
B382344		5.94	0.213		<0.5	7.36	110	1330	3.0	14	2.66	<0.5	8	186	81	3.01
B382345		3.28	0.086		0.5	7.14	84	1220	2.8	4	2.70	<0.5	9	124	69	2.66
B382346		2.38	0.068		<0.5	7.05	423	1060	2.6	9	2.32	<0.5	8	153	72	2.79
B382347		5.48	0.083		<0.5	7.22	366	1380	2.7	7	2.24	<0.5	9	102	78	2.43
B382348		5.70	0.027		<0.5	7.82	68	1620	3.2	<2	2.77	<0.5	9	146	64	2.86
B382349		0.06	0.032													
B382350		0.12	2.66		<0.5	7.58	2120	700	12.5	<2	0.02	<0.5	<1	142	102	3.55
B382351		2.80	3.44		<0.5	6.23	4530	1330	2.2	403	2.20	<0.5	46	120	179	3.07
B382352		2.76	0.101		0.5	7.56	444	1400	2.9	6	2.46	<0.5	10	154	86	2.61
B382353		2.12	0.059		<0.5	7.48	186	1420	2.6	3	2.89	<0.5	11	98	69	2.64
B382354		4.22	0.105		1.0	7.57	112	1420	2.9	6	2.58	<0.5	11	148	108	2.99
B382355		3.22	0.246		0.8	6.87	1565	1320	2.8	15	2.42	<0.5	13	112	157	2.90
B382356		2.10	<0.005		<0.5	0.11	<5	20	<0.5	<2	19.15	<0.5	1	10	4	0.11
B382357		1.52	0.109		0.5	7.16	138	1480	3.0	10	3.31	<0.5	11	112	66	2.66
B382358		3.38	0.120		0.5	6.62	214	1440	2.7	28	2.32	<0.5	10	182	95	2.68
B382359		1.74	0.129		<0.5	6.93	91	1410	2.6	<2	2.19	<0.5	9	112	80	2.63
B382360		2.72	0.087		<0.5	7.09	129	1640	3.1	2	2.36	<0.5	10	153	75	2.69
B382361		0.90	0.059		<0.5	7.14	52	1490	3.0	<2	2.76	<0.5	11	110	102	2.55
B382362		0.82	0.138		<0.5	7.00	63	1480	3.0	4	3.08	<0.5	11	176	98	2.56
B382363		2.96	0.059		<0.5	6.88	71	1620	3.0	14	2.35	<0.5	10	108	54	2.62
B382364		2.12	0.061		1.7	6.84	34	710	2.8	<2	3.20	10.2	9	160	76	2.15
B382365		5.64	1.770		<0.5	7.36	322	1380	3.0	28	2.48	<0.5	11	118	99	2.69
B382366		5.28	0.042		<0.5	6.69	94	1310	3.0	<2	2.64	<0.5	10	170	79	2.38
B382367		6.30	0.419		<0.5	6.69	2740	1460	2.7	138	2.31	<0.5	14	115	77	2.60
B382368		6.74	0.027		<0.5	6.79	110	1260	2.7	<2	2.42	<0.5	9	135	71	2.37
B382369		0.04	0.028													
B382370		0.10	4.42		8.7	7.44	<5	480	0.9	<2	2.71	0.9	20	23	125	4.12
B382371		5.82	0.029		<0.5	6.85	14	1340	2.8	<2	3.02	<0.5	11	120	25	2.86
B382372		6.30	0.033		<0.5	7.60	198	1380	2.9	<2	2.59	<0.5	11	154	41	2.94
B382373		6.66	0.026		<0.5	6.89	44	1340	2.9	<2	2.50	<0.5	11	119	37	2.91

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B382334		0.01	3.61	0.90	205	15	1.60	20	570	17	0.43	6	456	0.28	41	10
B382335		0.01	3.48	0.85	322	1	1.58	19	590	28	0.76	16	429	0.28	40	10
B382336		<0.01	0.04	11.45	158	<1	0.02	5	440	<2	0.01	<5	105	<0.01	2	<10
B382337		0.01	3.69	0.89	255	3	1.68	23	610	18	0.27	7	497	0.31	45	10
B382338		0.01	3.64	0.94	263	1	1.72	19	580	19	0.20	14	487	0.28	39	10
B382339		0.01	3.59	0.90	224	1	1.79	21	620	18	0.26	7	519	0.31	41	<10
B382340		0.01	3.91	0.71	207	11	1.46	14	470	31	0.21	11	394	0.22	29	10
B382341		0.01	3.62	0.83	192	1	1.48	17	530	23	0.26	7	418	0.26	35	10
B382342		<0.01	3.67	0.93	228	1	1.76	22	600	21	0.26	11	477	0.30	43	10
B382343		0.01	3.46	1.02	312	1	1.60	19	600	25	0.19	20	406	0.29	46	10
B382344		0.01	3.56	1.26	337	1	1.72	19	640	16	0.25	8	517	0.30	56	<10
B382345		0.01	3.63	1.07	384	2	1.28	18	630	23	0.35	13	384	0.29	55	10
B382346		0.01	3.61	1.03	251	6	1.16	15	550	16	0.60	13	332	0.25	48	20
B382347		0.01	3.68	0.91	211	3	1.60	19	580	17	0.33	8	471	0.27	40	10
B382348		0.01	3.72	1.10	303	1	1.99	23	690	16	0.23	<5	593	0.34	51	10
B382349																
B382350		0.09	3.16	0.38	70	2	0.09	11	310	32	0.02	147	139	0.25	104	20
B382351		<0.01	3.67	0.79	160	8	1.32	14	550	14	1.06	9	421	0.25	38	10
B382352		0.01	3.61	1.01	223	2	1.81	20	660	18	0.33	<5	491	0.32	47	30
B382353		0.01	3.95	1.05	273	1	1.76	15	630	10	0.33	7	496	0.30	47	30
B382354		0.01	3.97	1.10	266	3	1.88	12	620	23	0.48	12	568	0.30	53	20
B382355		0.01	3.69	1.00	242	2	1.70	15	580	21	0.64	8	502	0.28	49	<10
B382356		0.01	0.03	10.95	164	<1	0.01	<1	530	2	<0.01	<5	110	<0.01	1	<10
B382357		0.01	3.40	1.07	296	3	1.84	14	640	15	0.20	5	525	0.31	48	20
B382358		0.01	3.70	0.94	224	3	1.62	15	600	11	0.38	9	459	0.29	46	10
B382359		0.01	3.29	0.99	274	2	1.50	16	610	28	0.27	11	428	0.28	44	20
B382360		0.01	3.42	0.99	283	1	1.76	20	690	29	0.30	6	525	0.33	47	10
B382361		0.01	3.63	0.90	273	1	1.66	19	660	23	0.40	<5	490	0.31	45	<10
B382362		0.01	3.84	0.88	274	4	1.62	18	630	18	0.37	8	484	0.30	45	10
B382363		0.01	3.55	1.04	379	2	2.00	20	670	17	0.17	5	547	0.32	48	<10
B382364		0.22	3.20	0.66	711	2	0.41	15	610	301	0.71	30	184	0.26	42	10
B382365		0.01	3.70	1.08	361	3	1.60	13	600	23	0.40	13	474	0.29	51	10
B382366		0.01	3.51	1.01	311	2	1.74	14	590	13	0.22	11	491	0.29	49	<10
B382367		0.01	3.46	0.93	230	3	1.71	16	600	15	0.34	9	491	0.28	45	10
B382368		0.01	3.06	1.00	276	3	1.72	11	560	15	0.18	<5	477	0.27	48	10
B382369																
B382370		0.03	2.19	1.30	947	13	1.62	13	860	19	0.64	<5	403	0.37	150	<10
B382371		0.01	3.21	1.17	449	2	1.85	12	620	18	0.11	<5	561	0.30	58	10
B382372		0.01	3.43	1.23	357	1	1.85	13	650	17	0.18	<5	558	0.30	59	<10
B382373		0.01	3.17	1.30	408	2	1.96	13	660	19	0.10	<5	563	0.31	61	<10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B382334		19
B382335		37
B382336		7
B382337		28
B382338		21
B382339		20
B382340		18
B382341		23
B382342		28
B382343		27
B382344		28
B382345		52
B382346		31
B382347		18
B382348		27
B382349		
B382350		13
B382351		18
B382352		26
B382353		27
B382354		28
B382355		33
B382356		6
B382357		29
B382358		20
B382359		31
B382360		32
B382361		28
B382362		24
B382363		27
B382364		1665
B382365		29
B382366		26
B382367		22
B382368		25
B382369		
B382370		97
B382371		49
B382372		39
B382373		44

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1	ME-ICP61 Fe % 0.01
B382374		4.42	0.626		<0.5	6.90	1795	1360	2.9	7	2.47	<0.5	18	164	41	3.03
B382375		5.08	0.027		<0.5	6.34	65	1500	2.9	<2	2.39	<0.5	11	103	43	2.46
B382376		1.94	<0.005		<0.5	0.14	<5	20	<0.5	<2	19.60	<0.5	1	27	2	0.15
B382377		2.94	0.034		<0.5	7.23	84	1550	2.9	<2	2.10	<0.5	11	103	54	2.68
B382378		3.16	0.062		<0.5	7.35	335	1480	3.0	<2	2.43	<0.5	11	160	68	2.69
B382379		5.34	0.027		<0.5	6.62	62	1470	2.7	<2	2.64	<0.5	10	106	30	2.35
B382380		3.60	0.062		<0.5	6.76	690	1400	2.5	<2	2.50	<0.5	10	150	23	2.42
B382381		1.00	0.018		<0.5	6.63	20	1380	2.3	<2	3.03	<0.5	12	102	30	2.35
B382382		1.02	0.036		<0.5	6.83	35	1440	2.4	2	3.03	<0.5	11	150	34	2.53
B382383		2.72	0.061		<0.5	7.18	16	1620	2.9	10	2.60	<0.5	10	116	49	2.68
B382384		3.08	0.034		<0.5	7.12	87	1560	2.9	<2	2.51	<0.5	11	142	50	2.68
B382385		3.58	0.007		<0.5	6.35	37	1620	3.0	<2	2.71	<0.5	12	104	11	2.70
B382386		2.12	0.009		<0.5	6.98	19	1360	2.7	<2	2.84	<0.5	11	150	15	2.82

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W
	Units	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm
	LOR	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10
B382374		0.01	3.52	1.18	384	3	1.86	15	650	17	0.21	<5	553	0.31	61	10
B382375		0.01	3.21	0.86	290	1	1.96	20	650	20	0.13	5	551	0.32	44	<10
B382376		<0.01	0.04	11.15	150	<1	0.02	1	490	2	0.01	<5	114	<0.01	2	<10
B382377		0.01	3.65	1.01	298	2	1.90	20	660	19	0.13	8	521	0.32	45	10
B382378		0.01	3.45	1.05	280	2	1.88	20	660	17	0.10	<5	519	0.32	46	20
B382379		0.01	3.30	0.94	324	2	1.72	20	630	19	0.11	11	520	0.30	43	30
B382380		0.01	3.16	0.96	325	13	1.74	15	610	21	0.06	9	496	0.28	41	20
B382381		0.01	3.03	0.90	319	1	1.80	15	550	16	0.08	7	514	0.27	39	30
B382382		0.01	3.08	0.94	329	2	1.95	20	600	18	0.13	6	531	0.29	40	30
B382383		0.01	3.26	1.01	309	3	1.86	22	700	19	0.14	<5	559	0.33	46	20
B382384		0.02	3.09	1.06	336	2	1.71	21	690	19	0.15	15	540	0.33	45	30
B382385		0.01	2.80	0.99	379	2	1.90	22	730	20	0.05	6	594	0.34	48	10
B382386		0.01	3.02	1.29	470	2	1.73	14	630	20	0.05	<5	571	0.29	55	10

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 9-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062470

Sample Description	Method	ME-ICP61
	Analyte	Zn
	Units	ppm
	LOR	2
B382374		45
B382375		38
B382376		7
B382377		40
B382378		32
B382379		39
B382380		39
B382381		37
B382382		39
B382383		39
B382384		44
B382385		53
B382386		53

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da J-AUG-2005
Account: STRGOL

CERTIFICATE VA05062471

Project: Dublin Gulch-1735

P.O. No.:

This report is for 53 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 27-JUL-2005.

The following have access to data associated with this certificate:


DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers
LOG-24	Pulp Login - Rcd w/o Barcode
SPL-21d	Split sample - duplicate

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES



To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B382387		4.14	0.046			<0.5	6.52	120	1470	2.9	4	2.19	<0.5	11	70	59
B382388		6.92	0.084	0.213	0.448	0.6	7.13	485	1650	2.8	14	2.06	<0.5	10	30	58
B382389		0.04	0.109													
B382390		0.12	0.764			2.1	7.06	<5	460	0.7	<2	1.81	<0.5	26	104	2050
B382391		3.58	0.094			<0.5	7.08	152	1720	2.8	2	2.13	<0.5	10	62	54
B382392		1.32	0.025			<0.5	7.92	103	1700	3.0	<2	2.30	<0.5	10	30	29
B382393		1.74	0.042			<0.5	7.14	200	1680	2.9	<2	1.73	<0.5	9	61	47
B382394		1.96	0.102			<0.5	7.00	273	1660	2.7	<2	1.87	<0.5	10	24	60
B382395		3.54	0.036			<0.5	6.86	229	1710	2.9	<2	1.82	<0.5	11	58	43
B382396		2.48	<0.005			<0.5	0.11	<5	20	<0.5	<2	19.90	<0.5	2	2	2
B382397		2.62	0.044			<0.5	7.05	288	1540	2.6	2	2.02	<0.5	8	64	37
B382398		2.52	0.272			1.2	7.32	601	1320	2.7	6	1.79	0.7	9	27	91
B382399		0.94	0.044			<0.5	7.44	251	1750	2.9	<2	1.52	<0.5	10	66	50
B382400		1.06	0.156			0.7	7.22	514	1210	2.6	4	2.73	<0.5	11	44	118
B382401		1.02	0.029			<0.5	7.61	267	1810	3.2	<2	1.70	<0.5	10	64	51
B382402		0.88	0.025			<0.5	7.37	287	1720	3.0	<2	1.47	<0.5	9	27	60
B382403		2.54	0.161			<0.5	6.51	444	1140	2.6	5	2.32	<0.5	9	70	71
B382404		2.58	0.125			<0.5	7.31	388	1500	3.0	25	2.05	<0.5	10	29	41
B382405		2.72	0.086			<0.5	6.94	306	1540	2.9	5	1.92	<0.5	8	62	48
B382406		2.78	0.023			0.6	7.22	316	1360	3.1	<2	1.58	<0.5	7	64	69
B382407		2.70	0.159			<0.5	7.52	438	1620	3.0	9	1.65	<0.5	8	19	75
B382408		6.36	0.165			5.0	7.26	1405	710	3.0	9	1.24	13.0	14	24	61
B382409		0.04	0.149													
B382410		0.12	1.380			<0.5	6.60	1250	700	5.8	<2	0.01	<0.5	6	204	39
B382411		5.36	0.220			5.1	7.24	1235	1040	2.6	5	1.30	<0.5	12	71	91
B382412		6.02	0.159			0.9	6.91	961	1640	2.5	12	1.57	<0.5	14	27	105
B382413		6.26	0.076			<0.5	7.12	631	1800	2.8	7	2.06	<0.5	12	79	73
B382414		4.46	0.075			<0.5	6.84	288	1680	2.8	10	2.14	<0.5	13	29	95
B382415		4.78	0.057			<0.5	7.55	641	1710	2.9	<2	2.28	<0.5	9	63	54
B382416		2.56	<0.005			<0.5	0.15	<5	20	<0.5	<2	19.40	<0.5	<1	3	4
B382417		1.90	0.329			0.7	7.25	350	1720	2.7	28	2.00	<0.5	19	67	101
B382418		1.64	0.302			<0.5	7.47	347	1840	2.7	15	2.35	<0.5	13	32	114
B382419		2.58	0.053			<0.5	7.40	193	1650	2.8	<2	2.17	<0.5	11	71	67
B382420		2.00	0.077			<0.5	7.44	236	1580	2.9	6	2.11	<0.5	11	27	68
B382421		0.92	0.032			<0.5	7.11	98	1660	3.1	<2	2.27	<0.5	11	67	53
B382422		0.90	0.056			<0.5	7.60	86	1740	3.2	<2	2.27	<0.5	10	29	46
B382423		3.40	0.086			<0.5	7.26	206	1500	3.1	11	1.88	<0.5	9	62	42
B382424		3.34	0.080			<0.5	7.39	214	1660	2.9	14	2.20	<0.5	10	26	37
B382425		3.48	0.043			<0.5	6.96	226	1580	3.0	<2	2.30	<0.5	9	63	44
B382426		2.82	0.047			<0.5	6.95	475	1520	2.6	2	2.49	<0.5	11	69	47

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B382387		2.68	0.01	3.32	0.92	313	2	1.63	18	610	23	0.12	<5	461	0.31	46
B382388		2.60	0.01	3.61	0.82	270	2	1.66	21	650	23	0.14	<5	495	0.31	39
B382389																
B382390		5.15	0.01	1.66	1.32	429	4	3.10	52	640	16	0.58	<5	211	0.30	94
B382391		2.61	0.01	3.53	0.84	261	2	1.74	21	660	24	0.10	<5	516	0.32	41
B382392		2.71	0.01	3.49	0.89	308	2	1.78	24	680	26	0.08	<5	527	0.33	44
B382393		2.39	0.01	3.74	0.62	237	1	1.60	19	610	32	0.03	<5	412	0.30	37
B382394		2.35	0.01	3.41	0.70	232	2	1.26	15	590	14	0.01	13	355	0.28	36
B382395		2.49	0.01	3.49	0.70	226	2	1.56	24	630	21	0.05	7	434	0.30	39
B382396		0.12	<0.01	0.03	11.30	152	<1	0.01	<1	540	<2	<0.01	<5	112	<0.01	1
B382397		2.38	0.02	3.43	0.56	292	1	1.40	19	630	28	0.01	19	352	0.29	36
B382398		2.55	0.04	4.06	0.42	447	3	0.77	13	640	119	0.08	23	183	0.27	38
B382399		2.60	0.01	3.57	0.64	188	2	1.57	23	650	33	0.02	18	395	0.31	40
B382400		3.02	0.02	2.97	0.93	446	1	1.14	30	660	31	0.06	9	356	0.32	65
B382401		2.59	0.01	3.74	0.75	210	2	1.62	22	660	20	0.03	<5	429	0.31	40
B382402		2.42	0.01	3.63	0.66	184	1	1.50	19	620	22	0.03	<5	382	0.30	38
B382403		2.17	0.01	3.15	0.37	270	2	1.28	17	640	32	0.04	11	244	0.29	39
B382404		2.55	0.01	3.37	0.60	254	2	1.44	20	620	36	0.01	9	344	0.31	39
B382405		2.28	0.01	3.61	0.68	216	1	1.40	19	560	17	0.04	5	381	0.27	34
B382406		1.87	0.01	4.19	0.46	148	2	1.42	11	470	20	0.02	<5	345	0.23	28
B382407		2.06	0.01	4.69	0.56	204	2	1.14	16	500	29	0.01	11	357	0.23	28
B382408		2.78	0.18	3.28	0.47	764	4	0.28	17	560	607	0.29	197	147	0.26	34
B382409																
B382410		3.73	0.06	2.56	0.34	87	3	0.10	20	340	28	0.02	119	91	0.26	92
B382411		2.94	0.05	3.40	0.52	485	3	0.67	23	640	82	0.44	79	219	0.28	37
B382412		2.75	0.03	3.85	0.57	293	6	0.92	23	620	48	0.31	29	274	0.28	37
B382413		2.63	0.01	3.67	0.74	252	3	1.31	23	630	14	0.14	19	394	0.32	41
B382414		2.71	0.01	3.51	0.79	233	2	1.58	24	610	12	0.35	<5	466	0.32	41
B382415		2.60	0.01	3.46	0.84	244	3	1.52	23	630	14	0.22	<5	442	0.30	38
B382416		0.12	<0.01	0.04	11.20	158	<1	0.02	2	500	<2	<0.01	<5	117	<0.01	2
B382417		2.86	0.01	3.90	0.78	207	15	1.39	20	610	15	0.46	<5	415	0.30	38
B382418		2.85	0.01	4.42	0.83	225	2	1.44	27	670	15	0.48	<5	481	0.32	41
B382419		2.56	0.01	3.61	0.80	204	5	1.58	20	630	4	0.28	<5	491	0.30	37
B382420		2.74	0.01	3.47	0.78	221	2	1.58	22	610	9	0.43	<5	455	0.30	37
B382421		2.59	0.01	3.30	0.78	233	1	1.62	21	600	12	0.23	<5	462	0.31	38
B382422		2.74	0.01	3.40	0.84	246	2	1.68	20	620	11	0.24	<5	484	0.33	40
B382423		2.36	0.01	3.71	0.75	233	2	1.49	18	560	27	0.18	<5	390	0.27	34
B382424		2.58	0.01	3.43	0.79	267	1	1.48	19	620	19	0.16	<5	434	0.30	37
B382425		2.28	0.01	3.56	0.66	247	3	1.48	19	590	21	0.20	6	410	0.29	37
B382426		2.41	0.01	3.37	0.70	265	3	1.34	22	590	16	0.24	8	403	0.28	35

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B382387		20	61
B382388		30	69
B382389			
B382390		<10	207
B382391		20	55
B382392		<10	75
B382393		10	80
B382394		40	44
B382395		10	57
B382396		<10	8
B382397		30	76
B382398		50	163
B382399		20	99
B382400		30	56
B382401		20	67
B382402		20	65
B382403		20	48
B382404		40	67
B382405		40	56
B382406		20	30
B382407		30	108
B382408		30	1865
B382409			
B382410		10	48
B382411		40	393
B382412		40	93
B382413		30	29
B382414		60	33
B382415		70	30
B382416		<10	9
B382417		570	26
B382418		50	29
B382419		50	26
B382420		10	30
B382421		20	32
B382422		10	31
B382423		40	38
B382424		30	41
B382425		30	44
B382426		20	42

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method Analyte Units LOR	WEI-21 Recvd Wt. kg 0.02	Au-AA23 Au ppm 0.005	Au-AA23 Au Check ppm 0.005	Au-AA23 Au Check ppm 0.005	ME-ICP61 Ag ppm 0.5	ME-ICP61 Al % 0.01	ME-ICP61 As ppm 5	ME-ICP61 Ba ppm 10	ME-ICP61 Be ppm 0.5	ME-ICP61 Bi ppm 2	ME-ICP61 Ca % 0.01	ME-ICP61 Cd ppm 0.5	ME-ICP61 Co ppm 1	ME-ICP61 Cr ppm 1	ME-ICP61 Cu ppm 1
B382427		2.24	0.020			<0.5	7.21	71	1600	2.9	<2	2.21	<0.5	8	28	18
B382428		1.82	0.112			<0.5	7.19	827	1600	2.8	18	2.56	<0.5	10	59	46
B382429		0.06	0.274													
B382430		0.12	NSS			<0.5	7.14	2040	740	11.7	<2	0.01	<0.5	1	144	99
B382431		3.16	0.156			<0.5	7.02	744	1360	2.6	16	2.24	<0.5	12	33	78
B382432		3.38	0.098			<0.5	6.75	801	1140	2.4	8	2.18	<0.5	12	59	58
B382433		3.70	0.647			<0.5	7.17	539	1640	2.6	15	2.24	<0.5	21	29	77
B382434		2.82	0.045			<0.5	6.77	482	1770	2.8	<2	2.32	<0.5	10	63	50
B382435		4.22	0.068			<0.5	6.48	186	1440	2.6	4	2.31	<0.5	10	28	59
B382436		2.14	<0.005			<0.5	0.12	<5	20	<0.5	<2	20.1	<0.5	1	4	2
B382437		4.06	0.008			<0.5	7.64	97	1670	2.9	<2	2.42	<0.5	9	30	30
B382438		2.76	0.052			1.0	6.80	475	1140	2.7	<2	2.44	1.4	9	63	46
B382439		2.48	0.029			1.2	7.07	122	1280	4.3	3	1.93	<0.5	6	26	27

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method	ME-ICP61	Hg-CV41	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	Fe	Hg	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V
	Units	%	ppm	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm
	LOR	0.01	0.01	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1
B382427		2.38	0.01	3.32	0.73	282	4	1.52	17	590	20	0.12	<5	444	0.29	35
B382428		2.44	0.01	3.26	0.73	260	1	1.50	19	600	16	0.24	<5	456	0.29	35
B382429																
B382430		3.41	0.09	2.93	0.37	68	3	0.08	11	320	21	0.02	154	140	0.23	100
B382431		2.32	0.01	3.57	0.69	194	3	1.41	23	530	18	0.33	9	398	0.26	33
B382432		2.24	0.01	3.01	0.66	211	2	1.50	18	640	14	0.35	<5	379	0.28	35
B382433		2.60	0.01	3.74	0.78	221	5	1.44	20	600	21	0.39	<5	447	0.29	36
B382434		2.54	0.01	3.59	0.76	250	2	1.55	21	650	20	0.26	<5	483	0.31	39
B382435		2.34	0.01	3.36	0.71	262	4	1.38	23	580	59	0.28	<5	430	0.29	36
B382436		0.11	<0.01	0.03	11.50	164	<1	0.01	<1	550	<2	<0.01	<5	112	<0.01	1
B382437		2.57	0.02	3.61	0.79	347	2	1.22	21	630	41	0.19	9	415	0.31	41
B382438		2.76	0.06	3.11	0.77	827	1	0.81	20	630	154	0.41	15	322	0.28	36
B382439		1.82	0.02	3.23	0.60	218	2	1.56	12	490	79	0.18	5	333	0.19	36

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 10-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05062471

Sample Description	Method / Analyte / Units / LOR	ME-ICP61 W ppm 10	ME-ICP61 Zn ppm 2
B382427		10	45
B382428		20	34
B382429			
B382430		10	17
B382431		40	23
B382432		30	30
B382433		30	26
B382434		20	41
B382435		10	90
B382436		<10	9
B382437		20	128
B382438		30	449
B382439		10	86

Comments: NSS is non-sufficient sample.

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Da -AUG-2005
Account: STRGOL

CERTIFICATE VA05063074

Project: Dublin Gulch-1735

P.O. No.:

This report is for 4 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 29-JUL-2005.

The following have access to data associated with this certificate:

DAVID HLADKY	JIM SPARLING	TERRY TUCKER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um
WSH-21	"Wash" crushers
WSH-22	"Wash" pulverizers

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Au-AA23	Au 30g FA-AA finish	AAS
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-ICP61	27 element four acid ICP-AES	ICP-AES

To: **STRATAGOLD CORPORATION**
ATTN: JIM SPARLING
701-475 HOWE ST
VANCOUVER BC V6C 2B3

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 13-AUG-2005
Account: STRGOL

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05063074

Sample Description	Method	WEI-21	Au-AA23	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Hg-CV41
	Analyte	Recvd Wt.	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Hg
	Units	kg	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm
	LOR	0.02	0.005	0.5	0.01	5	10	0.5	2	0.01	0.5	1	1	1	0.01	0.01
B380991		2.00	<0.005	<0.5	4.43	11	290	0.9	<2	0.30	<0.5	5	90	12	1.95	0.01
B380992		4.04	0.011	<0.5	4.11	39	280	0.9	<2	0.27	<0.5	6	131	18	1.68	<0.01
B380993		3.22	0.006	<0.5	3.22	51	200	0.8	<2	0.31	<0.5	4	91	21	1.58	<0.01
B380994		4.46	0.247	<0.5	4.73	69	290	1.0	<2	0.48	<0.5	7	156	22	2.50	<0.01

ALS Chemex
EXCELLENCE IN ANALYTICAL CHEMISTRY
ALS Canada Ltd.
212 Brooksbank Avenue
North Vancouver BC V7J 2C1
Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

STRATAGOLD CORPORATION
701-475 HOWE ST
VANCOUVER BC V6C 2B3

Finalized Date: 13-AUG-2005
Account: STRGOL

094876

Project: Dublin Gulch-1735

CERTIFICATE OF ANALYSIS VA05063074

Sample Description	Method	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
	Analyte	K	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sr	Ti	V	W	Zn
	Units	%	%	ppm	ppm	%	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	ppm
	LOR	0.01	0.01	5	1	0.01	1	10	2	0.01	5	1	0.01	1	10	2
B380991		1.26	0.49	150	<1	0.40	18	190	8	0.15	<5	56	0.21	36	<10	36
B380992		1.18	0.41	124	1	0.46	16	210	3	0.20	<5	61	0.19	35	10	23
B380993		0.97	0.36	130	<1	0.33	16	180	5	0.25	<5	59	0.13	28	<10	18
B380994		1.22	0.69	266	<1	0.57	24	230	9	0.42	<5	82	0.18	39	<10	41