Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8050

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

17-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR030
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
5	8R231495	22.8	0.665
27	8R232617	4.79	0.140

QC DATA:

Repeat:

5	8R231495	22.9	0.668

Standard:

OXI67	1.86	0.054

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

13-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8050
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR030
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R231491	40	0.4	8.25	25	665	<5	2.68	4	28	152	268	6.14	1.79	<10	1.75	458	<1	2.90	28	510	34	<5	<20	281	0.24	<10	176	<10	12	41
2	8R231492	30	0.2	7.97	310	395	<5	3.11	4	27	156	254	6.28	1.61	20	1.42	471	<1	2.30	29	470	32	10	<20	269	0.22	<10	163	<10	16	118
3	8R231493	75	0.8	9.12	140	375	<5	4.07	4	26	172	151	4.14	1.31	<10	1.85	377	<1	2.15	30	580	32	<5	<20	197	0.24	<10	154	<10	10	70
4	8R231494	90	0.2	8.15	190	495	<5	3.09	4	24	155	216	5.18	1.71	<10	1.55	425	<1	2.55	28	520	36	10	<20	187	0.24	<10	161	<10	9	45
5	8R231495	>1000	0.8	5.27	390	180	315	1.60	7	35	143	1229	>10	1.14	10	1.18	561	<1	1.96	32	580	30	30	60	80	0.18	<10	107	10	13	35
6	8R231496	10	0.2	7.03	15	1025	<5	1.17	2	7	151	21	1.79	3.51	40	0.38	429	2	3.25	18	460	44	<5	<20	267	0.17	<10	31	<10	13	42
7	8R231497	60	0.4	7.74	140	490	<5	3.41	4	30	141	347	5.47	1.80	<10	1.67	448	<1	3.08	31	460	56	5	<20	176	0.22	<10	153	<10	12	97
8	8R231498	170	0.4	7.84	10	400	<5	3.24	4	26	151	233	5.40	1.70	<10	2.04	403	<1	2.87	30	590	34	<5	<20	277	0.25	<10	170	<10	13	38
9	8R231499	25	0.4	8.47	10	280	<5	3.15	4	26	164	328	5.47	1.63	<10	2.04	360	<1	2.73	32	450	34	<5	<20	266	0.24	<10	164	<10	11	28
10	8R231500	15	0.2	8.04	5	450	<5	4.15	4	28	136	255	5.17	1.25	<10	2.24	716	<1	3.00	32	430	34	<5	<20	190	0.21	<10	159	<10	11	52
11	8R232601	15	<0.2	8.08	5	720	<5	3.34	4	24	162	177	4.58	1.75	<10	1.95	528	<1	2.75	28	400	62	<5	<20	280	0.19	<10	141	<10	10	99
12	8R232602	50	<0.2	7.55	<5	890	<5	1.96	3	16	182	137	3.72	2.78	<10	1.80	208	<1	2.39	25	320	36	<5	<20	272	0.16	<10	113	<10	7	21
13	8R232603	60	<0.2	8.09	75	650	<5	2.75	4	26	168	175	5.19	2.94	<10	2.64	416	<1	1.79	30	470	34	<5	<20	134	0.22	<10	167	<10	10	52
14	8R232604	70	0.2	7.87	135	745	<5	2.86	3	23	143	317	4.84	2.93	<10	2.15	383	1	0.83	27	470	34	5	<20	103	0.19	<10	149	<10	9	41
15	8R232605	10	0.2	7.65	260	535	<5	4.37	3	24	200	167	4.91	1.95	<10	2.23	610	<1	2.07	32	420	36	10	<20	195	0.22	<10	168	<10	11	45
16	8R232606	25	<0.2	7.51	70	630	<5	2.48	4	25	206	192	5.76	3.02	<10	2.48	416	<1	1.83	30	430	34	<5	<20	140	0.23	<10	177	<10	11	45
17	8R232607	<5	<0.2	7.21	20	915	<5	1.91	3	19	211	120	4.03	2.43	<10	1.96	283	1	2.46	26	420	42	<5	<20	200	0.19	<10	135	<10	7	30
18	8R232608	65	0.4	7.66	75	1075	<5	2.60	3	20	176	383	4.75	2.20	20	1.68	213	<1	2.21	26	430	36	5	<20	200	0.18	<10	130	<10	11	19
19	8R232609	10	0.4	7.65	65	2470	<5	1.01	3	24	198	368	4.75	3.27	30	1.39	168	8	2.45	27	380	36	<5	<20	148	0.16	<10	141	<10	8	16
20	8R232610	5	<0.2	7.41	50	6305	<5	0.71	2	11	155	90	1.82	3.26	60	0.34	235	1	3.75	19	300	40	<5	<20	275	0.06	<10	23	<10	7	18
21	8R232611	<5	<0.2	7.12	215	990	<5	1.36	3	27	195	194	5.01	3.26	10	1.69	494	5	1.53	31	440	34	35	<20	85	0.13	<10	169	<10	9	34
22	8R232612	20	0.2	7.44	90	510	<5	2.20	3	17	172	356	4.41	2.56	<10	1.69	247	3	2.59	28	390	46	5	<20	136	0.17	<10	188	<10	6	67
23	8R232613	20	0.6	6.35	430	845	<5	3.58	3	44	165	653	6.14	3.33	<10	0.44	151	4	1.97	35	270	28	55	<20	116	0.06	<10	146	<10	4	9
24	8R232614	20	0.8	7.88	470	710	<5	1.81	3	21	181	660	4.73	2.03	10	1.34	187	3	3.20	31	440	40	25	<20	129	0.22	<10	230	<10	12	27
25	8R232615	5	0.4	6.90	180	4560	<5	2.62	2	7	168	149	1.57	3.05	110	0.28	105	3	3.83	17	280	42	10	<20	283	0.06	<10	23	<10	9	8

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R232616	<5	0.2	7.73	250	1145	<5	1.56	3	24	224	157	5.50	2.62	10	1.21	227	<1	1.39	26	540	38	15	<20	90	0.25	<10	191	<10	7	19
27	8R232617	>1000	3.0	5.17	15	290	<5	1.06	2	10	30	56	3.01	4.86	<10	0.13	152	363	0.66	42	490	158	10	<20	645	0.05	<10	39	<10	4	311
28	8R232618	15	0.6	7.64	15	1755	<5	2.40	3	19	212	208	4.82	2.82	20	2.06	186	2	1.99	27	410	40	<5	<20	170	0.20	<10	148	<10	7	20
29	8R232619	5	<0.2	8.70	370	1335	<5	3.45	3	24	206	220	4.45	2.52	20	1.60	184	1	1.13	28	480	44	20	<20	91	0.21	<10	184	<10	9	16
30	8R232620	5	0.2	7.87	35	865	<5	2.39	4	27	171	254	5.69	2.42	<10	1.97	169	<1	2.17	29	420	38	<5	<20	172	0.23	<10	188	<10	6	19
31	8R232621	10	0.4	7.25	320	1080	<5	1.31	3	21	207	470	4.69	3.22	10	1.59	209	9	1.55	28	390	42	20	<20	88	0.14	<10	179	<10	5	62
32	8R232622	<5	<0.2	7.11	90	5055	<5	1.20	2	6	132	80	1.47	2.91	70	0.23	107	<1	3.91	15	280	40	<5	<20	291	0.05	<10	13	<10	6	10
33	8R232623	5	0.2	7.73	90	1190	<5	0.68	3	17	176	193	4.40	3.66	<10	1.75	212	7	1.94	28	470	46	5	<20	97	0.14	<10	194	<10	4	54
34	8R232624	<5	0.2	7.25	115	850	<5	0.83	3	17	232	180	4.58	3.39	<10	2.02	246	7	1.93	29	430	40	5	<20	95	0.18	<10	193	<10	5	43
35	8R232625 Dup	<5	0.4	7.22	115	830	<5	0.81	3	16	239	183	4.39	3.30	<10	1.97	243	5	1.86	28	410	40	5	<20	91	0.17	<10	184	<10	5	41
QC DATA:																															
Repeat:																															
1	8R231491	30	0.6	8.09	25	660	<5	2.67	4	27	159	307	5.96	1.87	10	1.72	441	<1	3.05	28	500	34	<5	<20	283	0.26	<10	171	<10	13	42
4	8R231494	90																													
8	8R231498	200																													
10	8R231500	15	0.4	8.25	5	445	<5	4.03	4	27	138	286	5.19	1.25	<10	2.30	718	<1	3.01	32	430	34	<5	<20	189	0.21	<10	159	<10	11	50
19	8R232609	10	0.4	7.84	75	2545	<5	1.04	3	25	211	429	4.97	3.33	40	1.42	175	8	2.61	28	400	38	<5	<20	154	0.17	<10	155	<10	8	18
Resplit:																															
1	8R231491	55	0.4	8.10	25	670	<5	2.82	4	28	177	312	6.39	1.95	10	1.76	495	<1	3.21	29	510	36	<5	<20	301	0.28	<10	193	<10	14	44
Standard:																															
Stsd3			0.3	5.78	35	1490	<5	2.40	4	21	67	45	4.56	1.37	30	1.34	2735	5	1.15	43	1740	46	<5	<20	242	0.43	<10	137	<10	25	213
SF30		815																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/ap/nw
df/2_TD8048S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer