Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8076

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

22-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR061
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
16	X47022	1.24	0.036
29	X47036	20.4	0.595

QC DATA:

Repeat:

16	X47022	1.26	0.037

Standard:

OXI67	1.87	0.055
SK43	4.00	0.117

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

21-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8076
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR061
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X47007	45	0.6	7.09	20	1060	<5	0.12	2	4	165	220	1.84	1.97	20	0.15	34	6	0.62	19	170	66	15	<20	55	0.19	<10	57	<10	5	4
2	X47008	35	0.6	7.69	20	1235	<5	0.12	3	7	148	508	3.94	2.08	20	0.15	30	3	0.63	20	610	84	15	<20	66	0.28	<10	61	<10	9	6
3	X47009	175	0.8	6.89	40	1310	<5	0.60	2	8	158	425	3.13	2.58	50	0.57	84	4	2.81	20	460	78	<5	<20	238	0.28	<10	45	<10	23	20
4	X47010 Dup	185	0.8	6.64	40	1340	<5	0.57	2	7	131	409	2.95	2.42	50	0.54	77	3	2.70	20	460	74	<5	<20	235	0.25	<10	42	<10	21	24
5	X47011	55	0.4	7.02	40	1630	<5	0.14	2	6	140	289	2.09	2.46	40	0.18	41	3	0.85	18	450	70	15	<20	119	0.23	<10	43	<10	10	8
6	X47012	165	0.6	7.20	60	1370	<5	0.12	2	5	178	234	2.01	2.62	30	0.15	39	3	0.64	19	370	82	30	<20	106	0.27	<10	39	<10	11	5
7	X47013	75	1.0	6.61	25	1670	<5	0.38	2	7	143	390	2.85	2.98	40	0.62	95	3	2.18	19	390	72	<5	<20	142	0.22	<10	38	<10	14	16
8	X47014	20	0.4	6.59	30	2495	<5	0.27	2	6	140	541	2.64	2.78	30	0.48	88	6	1.39	19	350	74	5	<20	109	0.15	<10	43	<10	8	14
9	X47015	55	0.6	7.50	20	1615	20	0.23	2	10	180	440	2.36	3.09	50	0.52	166	3	0.70	22	360	86	5	<20	128	0.20	<10	44	<10	21	16
10	X47016	455	1.2	6.89	35	1795	<5	0.10	2	3	208	123	1.31	3.18	40	0.12	32	3	0.65	20	250	74	15	<20	95	0.16	<10	31	<10	11	6
11	X47017	60	0.6	6.44	85	1445	<5	0.07	2	2	127	203	1.45	3.16	30	0.05	22	3	0.61	18	220	74	25	<20	62	0.02	<10	7	<10	6	6
12	X47018	<5	0.6	6.95	15	525	<5	0.47	2	6	131	23	1.89	4.19	40	0.20	261	4	3.80	21	250	66	<5	<20	139	0.20	<10	22	<10	15	30
13	X47019	40	0.6	6.44	85	1660	<5	0.07	2	2	159	271	1.69	3.46	30	0.05	28	7	0.68	19	230	80	25	<20	78	0.03	<10	8	<10	7	6
14	X47020	200	2.2	6.27	235	2030	10	0.10	3	4	105	559	3.98	4.63	30	0.09	29	4	0.72	20	630	122	25	<20	173	0.07	<10	32	<10	21	22
15	X47021	160	1.8	7.02	140	1955	15	0.10	2	3	77	319	2.33	3.99	50	0.09	20	3	0.67	20	490	90	20	<20	202	0.08	<10	34	<10	17	15
16	X47022	>1000	1.4	6.84	235	1935	25	0.09	3	3	90	253	2.40	4.03	40	0.09	21	3	0.66	20	500	74	20	<20	180	0.07	<10	34	<10	16	17
17	X47023	65	1.8	6.88	75	2020	5	0.10	2	3	90	150	1.58	4.83	50	0.10	41	2	0.71	19	380	74	25	<20	215	0.08	<10	37	<10	14	8
18	X47025	45	1.8	7.24	55	2125	<5	0.10	2	3	93	134	1.61	4.76	50	0.10	31	2	0.75	20	430	80	25	<20	246	0.10	<10	41	<10	12	6
19	X47026	95	2.4	6.94	100	2360	<5	0.10	2	3	90	171	1.68	4.96	50	0.10	36	3	0.74	18	400	74	25	<20	260	0.11	<10	41	<10	12	7
20	X47027	350	2.8	4.66	70	5435	10	0.08	2	9	208	663	3.82	4.24	10	0.09	85	9	0.75	14	450	72	10	<20	118	0.09	<10	76	<10	8	37
21	X47028	240	2.0	6.85	30	2375	<5	0.10	2	3	96	210	1.67	5.28	40	0.10	27	2	0.74	18	410	74	15	<20	263	0.10	<10	37	<10	10	5
22	X47029	90	2.2	6.44	40	2020	<5	0.09	2	3	77	97	1.34	4.77	50	0.11	28	2	0.70	17	350	68	20	<20	280	0.10	<10	37	<10	9	4
23	X47030	55	4.0	7.18	55	2455	5	0.10	2	4	104	128	1.93	6.10	50	0.10	38	4	0.80	19	360	82	20	<20	292	0.11	<10	41	<10	9	3
24	X47031	55	0.8	6.37	40	2425	<5	0.08	3	18	169	627	4.89	2.77	20	0.09	150	7	0.64	23	500	72	15	<20	82	0.10	<10	56	<10	8	121
25	X47032	15	0.4	6.53	25	3415	<5	0.08	2	14	197	341	3.25	3.09	20	0.12	166	6	0.67	22	240	74	10	<20	111	0.11	<10	47	<10	5	59

ECO TECH LABORATORY LTD. **ICP CERTIFICATE OF ANALYSIS AW 2009-8076** **Bushmaster Exploration**

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X47033	40	0.4	7.52	40	1335	<5	0.11	3	18	146	375	4.59	2.27	40	0.18	301	2	0.62	25	400	82	20	<20	72	0.19	<10	27	<10	9	57
27	X47034	50	0.6	8.38	35	1395	<5	0.14	4	13	120	609	4.63	2.22	40	0.18	74	1	0.64	28	660	90	10	<20	65	0.26	<10	44	<10	10	39
28	X47035	35	1.0	8.70	15	1725	<5	0.13	2	6	100	169	1.22	2.63	40	0.15	24	5	0.64	28	320	86	10	<20	98	0.30	<10	38	<10	13	5
29	X47036	>1000	4.1	2.87	1095	215	5	2.37	4	20	82	118	4.50	0.93	<10	0.75	591	38	0.89	66	290	1276	5	<20	74	0.04	<10	70	<10	4	297
30	X47037	20	0.4	6.87	10	1745	<5	0.08	1	5	154	56	0.66	3.47	40	0.06	93	3	0.70	22	110	78	15	<20	69	0.04	<10	6	<10	7	2
31	X47038	20	0.6	6.76	10	1725	<5	0.08	1	4	146	71	0.76	3.43	40	0.05	91	4	0.69	21	100	78	10	<20	65	0.03	<10	5	<10	6	5
32	X47039	20	1.2	6.70	15	1795	<5	0.10	2	7	181	159	1.84	3.46	40	0.08	99	4	0.70	22	210	80	20	<20	70	0.03	<10	8	<10	7	15
33	X47040	25	0.4	6.79	20	2330	<5	0.19	2	3	106	118	1.20	3.36	50	0.18	39	2	0.78	20	120	76	15	<20	78	0.06	<10	10	<10	6	9
34	X47041	20	0.6	6.72	90	1930	<5	0.18	2	4	119	169	2.22	3.32	40	0.18	55	3	1.03	20	150	86	15	<20	98	0.09	<10	23	<10	6	11
QC DATA:																															
Repeat:																															
1	X47007	50	0.4	7.13	20	995	<5	0.11	2	4	158	213	1.59	1.89	20	0.15	30	5	0.59	19	170	64	15	<20	52	0.18	<10	52	<10	4	3
10	X47016	410	1.2	6.65	35	1710	<5	0.10	2	3	203	117	1.29	3.00	40	0.11	32	3	0.64	19	240	74	15	<20	93	0.17	<10	30	<10	10	5
19	X47026	85	2.2	7.19	110	2425	<5	0.10	2	3	84	177	1.53	4.80	50	0.11	33	3	0.71	20	440	78	25	<20	255	0.11	<10	38	<10	11	7
Resplit:																															
1	X47007	45	0.4	6.93	20	965	<5	0.10	2	4	152	208	1.66	1.79	20	0.15	29	4	0.56	19	180	64	15	<20	50	0.18	<10	50	<10	4	4
Standard:																															
Stsd3			0.4	5.89	30	1410	<5	2.51	4	22	78	35	4.27	1.43	30	1.40	2630	8	1.17	48	1710	62	<5	<20	229	0.44	<10	129	<10	34	199
SF30		820																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
dt/2_TD8075S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer