Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8063

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

17-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR040
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
10	8R232740	1.62	0.047
29	8R232759	1.68	0.049
QC DATA:			
Repeats:			
10	8R232740	1.50	0.044
29	8R232759	1.82	0.053
Standard:			
Oxi67		1.81	0.053

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada

16-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8063 R
Total Digest
REVISED

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR040
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R232731	20	0.2	5.63	5	1010	<5	1.00	3	10	178	288	3.92	2.31	30	0.55	184	1	2.33	14	300	66	<5	<20	166	0.10	<10	9	<10	24	147
2	8R232732	40	0.6	7.84	<5	920	20	1.49	2	12	203	534	4.97	2.04	30	0.97	190	2	2.59	16	410	70	<5	<20	181	0.14	<10	9	<10	26	33
3	8R232733	15	0.4	5.44	30	815	5	1.11	2	9	189	345	3.87	1.72	20	0.56	170	2	2.15	12	250	54	<5	<20	162	0.11	<10	3	<10	20	61
4	8R232734	5	2.0	7.02	20	4160	285	1.19	2	6	171	190	2.07	3.61	60	0.42	167	6	2.45	14	170	270	5	<20	189	0.05	<10	8	<10	10	57
5	8R232735	45	1.2	5.38	20	1025	65	1.34	3	8	196	532	3.54	2.35	20	0.41	193	2	1.68	12	230	106	10	<20	140	0.10	<10	3	<10	23	154
6	8R232736	5	0.4	5.86	30	915	5	1.10	2	8	150	242	4.03	2.15	30	0.43	210	<1	0.94	11	290	54	30	<20	132	0.14	<10	3	<10	30	42
7	8R232737	105	0.6	7.26	110	1240	<5	1.79	2	13	118	237	4.46	2.37	20	1.23	270	1	1.99	21	610	54	20	<20	251	0.28	<10	157	<10	12	23
8	8R232738	65	0.4	8.18	30	235	<5	1.89	3	22	71	371	7.31	1.97	10	1.49	329	<1	2.51	29	1030	60	<5	<20	261	0.37	<10	216	<10	16	32
9	8R232739	55	0.2	8.53	10	250	<5	3.23	3	34	84	314	6.01	1.64	10	2.91	676	<1	2.65	38	1630	66	<5	<20	182	0.62	<10	263	<10	26	47
10	8R232740	>1000	<0.2	9.13	15	325	5	1.45	3	31	76	273	6.54	2.79	10	3.27	336	<1	2.79	40	920	66	<5	<20	164	0.40	<10	246	<10	19	36
11	8R232741	* 460	<0.2	7.50	5	165	<5	0.75	2	19	55	375	6.94	2.54	<10	2.28	151	<1	2.82	24	750	56	<5	<20	141	0.38	<10	231	<10	8	23
12	8R232742	160	<0.2	9.05	5	140	<5	1.98	3	17	50	330	7.81	1.92	10	1.51	220	<1	2.74	22	880	64	<5	<20	206	0.41	<10	263	<10	12	24
13	8R232743	165	0.2	9.35	5	125	<5	2.29	3	19	56	395	7.17	1.57	<10	1.55	274	1	2.80	24	890	66	<5	<20	173	0.43	<10	267	<10	14	28
14	8R232744	610	0.2	8.31	<5	120	<5	2.90	2	34	76	26	3.97	3.96	10	2.03	537	2	3.96	83	1200	84	<5	<20	349	0.59	<10	86	<10	8	43
15	8R232745	65	0.2	9.67	40	170	<5	2.80	3	22	59	389	7.17	1.78	10	1.87	372	<1	2.46	28	880	70	<5	<20	190	0.39	<10	262	<10	14	32
16	8R232746	85	0.2	9.45	5	155	<5	3.88	3	22	64	194	5.74	1.02	10	1.86	580	<1	2.83	28	870	68	<5	<20	247	0.39	<10	230	<10	17	42
17	8R232747	90	0.2	9.79	5	165	<5	4.18	3	29	64	227	6.46	1.28	10	2.28	617	<1	2.65	35	930	74	<5	<20	226	0.43	<10	259	<10	19	44
18	8R232748	60	0.4	8.86	5	295	<5	3.77	3	31	71	236	5.97	1.33	10	2.06	619	<1	2.48	29	1400	64	<5	<20	252	0.53	<10	257	<10	23	45
19	8R232749	170	0.4	9.74	10	440	<5	2.85	3	30	63	427	6.61	1.62	20	2.08	533	<1	2.61	27	1740	62	<5	<20	251	0.65	<10	289	<10	26	43
20	8R232750	30	<0.2	9.42	<5	330	<5	3.59	3	54	74	258	5.56	1.72	10	2.67	739	<1	2.56	45	940	70	<5	<20	282	0.41	<10	240	<10	24	48
21	8R232751 Dup	100	<0.2	>10	5	165	<5	4.22	3	30	63	226	6.51	1.30	10	2.32	620	<1	2.68	35	950	74	<5	<20	228	0.43	<10	263	<10	20	48
22	8R232752	380	0.4	6.79	10	570	<5	0.44	2	11	83	347	5.41	2.30	20	0.76	62	<1	2.84	16	840	50	<5	<20	191	0.34	<10	194	<10	10	13
23	8R232753	90	0.4	6.63	10	6245	10	0.18	1	7	115	249	2.91	2.80	60	0.18	52	<1	2.67	14	280	52	<5	<20	219	0.07	<10	35	<10	5	8
24	8R232754	<5	0.2	5.98	15	440	<5	0.40	1	6	145	25	1.81	4.35	30	0.21	235	4	3.43	13	230	56	<5	<20	145	0.22	<10	27	<10	17	29
25	8R232755	150	<0.2	6.39	10	1150	<5	0.24	2	12	93	515	5.46	2.58	20	0.74	79	<1	2.86	16	680	50	<5	<20	143	0.17	<10	134	<10	6	15

* Based on 90g

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R232756	115	0.6	6.17	5	3250	15	0.25	2	9	126	402	3.99	2.88	30	0.39	50	<1	2.62	15	430	50	<5	<20	181	0.12	<10	80	<10	6	13
27	8R232757	320	1.8	9.26	<5	225	15	1.70	3	26	58	1904	6.19	2.13	10	1.71	130	<1	2.54	26	630	74	<5	<20	244	0.39	<10	247	<10	11	26
28	8R232758	185	0.8	6.95	15	4955	5	0.32	2	9	115	325	3.12	3.32	50	0.24	50	<1	2.78	16	360	56	<5	<20	256	0.10	<10	49	<10	6	13
29	8R232759	>1000	1.6	8.68	20	230	170	1.89	3	24	75	1102	7.13	1.74	40	1.71	238	<1	2.52	27	1210	70	<5	<20	281	0.49	<10	259	<10	20	39
30	8R232760	150	1.2	6.75	10	6160	15	0.24	1	7	143	329	2.26	3.26	60	0.20	43	1	2.56	16	290	58	<5	<20	243	0.08	<10	27	<10	6	10
31	8R232761	395	2.2	7.44	5	195	25	0.62	3	20	133	1044	9.40	2.81	30	2.98	188	<1	2.08	29	800	66	<5	<20	147	0.42	<10	257	<10	11	40
32	8R232762 Dup	220	0.8	6.95	15	4880	10	0.31	1	9	121	314	3.04	2.99	50	0.23	49	<1	2.70	16	350	56	<5	<20	243	0.10	<10	47	<10	6	11
33	8R232763	710	1.6	7.16	5	3370	10	0.35	2	10	108	785	3.39	2.83	30	0.36	60	<1	2.90	19	300	58	<5	<20	186	0.10	<10	47	<10	6	13
34	8R232764	335	2.2	8.93	5	815	5	1.99	3	32	69	1734	5.76	2.14	20	1.80	269	<1	2.87	36	790	70	<5	<20	228	0.39	<10	204	<10	17	38
35	8R232765	335	0.2	9.40	5	185	<5	3.27	3	38	60	584	5.98	1.66	20	2.54	559	<1	2.72	40	850	72	<5	<20	277	0.36	<10	236	<10	19	44
QC DATA:																															
Repeat:																															
1	8R232731	15	0.2	5.77	5	990	<5	0.98	3	9	170	282	3.98	2.28	30	0.52	176	<1	2.24	13	280	60	<5	<20	160	0.09	<10	7	<10	23	140
10	8R232740	>1000	0.2	9.70	15	315	5	1.40	2	30	71	264	6.32	2.69	10	3.20	322	<1	2.69	39	910	64	<5	<20	158	0.39	<10	235	<10	19	37
19	8R232749	140	0.8	9.98	10	430	<5	2.81	3	29	64	427	6.65	1.61	20	2.03	536	<1	2.61	27	1720	62	<5	<20	243	0.62	<10	289	<10	26	42
22	8R232752	440																													
27	8R232757	285																													
31	8R232761	370																													
33	8R232763	680																													
Resplit:																															
1	8R232731	15	0.4	5.64	<5	940	<5	0.90	2	9	155	279	3.69	2.18	30	0.53	169	<1	2.06	13	270	56	<5	<20	148	0.09	<10	7	<10	22	129
Standard:																															
Stsd3			0.4	5.88	20	1430	<5	2.46	3	20	64	39	4.31	1.42	30	1.41	2662	6	1.13	37	1670	44	<5	<20	225	0.43	<10	128	<10	32	203
OXE74		615																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8063s
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer