Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8067

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

20-Jul-09

No. of samples received: 34
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR046
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
3	X45070		1.24	0.036
25	X45093	*	1.10	0.032
QC DATA:				
Repeat:				
3	X45070		1.26	0.037
Resplit:				
1	X45068	*	1.13	0.033
Standard:				
Oxi67			1.87	0.055

* Based on 120g

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

20-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8067
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR046
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X45068	* 805	0.8	7.91	70	4475	10	0.06	1	1	99	114	1.01	3.26	80	0.10	15	8	0.49	23	200	34	35	<20	98	0.04	<10	9	<10	4	3
2	X45069	890	1.0	8.27	120	3280	25	0.06	2	1	93	156	1.27	2.69	90	0.15	15	9	0.46	21	320	32	50	<20	80	0.07	<10	14	<10	6	4
3	X45070	>1000	0.8	6.69	170	1525	20	0.07	1	5	113	2017	0.97	3.23	30	0.13	15	3	0.41	21	430	34	150	<20	98	0.10	<10	32	<10	9	28
4	X45071	290	0.6	7.04	195	1360	25	0.07	2	6	116	2069	1.33	2.67	30	0.13	16	3	0.42	28	580	40	110	<20	95	0.13	<10	37	<10	9	16
5	X45072	325	0.6	6.82	170	1430	15	0.07	1	6	105	1799	1.15	2.90	30	0.13	15	3	0.41	28	530	38	110	<20	92	0.13	<10	35	<10	9	14
6	X45073	* 615	1.0	7.20	210	975	10	0.16	2	9	201	1095	1.84	2.39	30	0.33	83	4	0.40	37	800	30	30	<20	48	0.20	<10	113	<10	12	28
7	X45074	735	7.8	7.08	25	745	<5	2.62	7	25	109	1300	5.81	1.42	10	1.83	750	56	1.90	196	830	296	15	<20	254	0.45	<10	129	<10	15	696
8	X45075	90	0.2	7.42	25	980	<5	0.22	2	17	345	1582	2.62	2.57	30	0.65	99	1	0.41	50	880	26	15	<20	33	0.28	<10	125	<10	15	18
9	X45076	655	0.4	7.53	55	820	<5	0.24	6	18	409	1605	3.22	2.42	30	0.72	123	2	0.51	57	840	32	20	<20	40	0.27	<10	143	<10	18	21
10	X45077	415	0.6	6.96	165	1565	20	0.15	2	7	167	2795	1.26	3.85	20	0.12	21	4	0.46	33	690	32	50	<20	116	0.08	<10	42	<10	10	25
11	X45078	95	0.4	8.00	30	815	<5	0.22	2	15	321	1698	2.44	2.78	30	0.46	93	2	0.43	41	840	32	15	<20	31	0.27	<10	126	<10	14	22
12	X45079	<5	<0.2	6.74	10	495	<5	0.49	1	5	129	33	1.72	4.63	30	0.19	221	3	3.25	11	290	54	<5	<20	134	0.23	<10	20	<10	15	28
13	X45080	135	0.4	7.16	20	820	90	0.27	3	19	346	305	3.64	2.49	30	0.68	153	3	0.53	41	760	40	10	<20	40	0.30	<10	134	<10	15	21
14	X45081	55	<0.2	7.90	20	820	<5	0.34	4	15	295	479	3.18	2.27	30	0.66	176	3	0.84	37	830	28	10	<20	80	0.36	<10	124	<10	16	24
15	X45082	145	<0.2	8.27	35	765	<5	0.27	3	18	290	1636	3.04	1.95	30	0.40	140	2	0.58	43	860	30	20	<20	50	0.39	<10	166	<10	15	17
16	X45083	410	0.2	8.34	10	1025	<5	0.24	2	14	298	2541	2.37	3.07	20	0.53	86	2	0.47	45	880	38	20	<20	54	0.21	<10	136	<10	14	15
17	X45084	120	0.2	7.28	10	960	<5	0.26	3	14	357	393	3.16	2.71	30	0.81	190	3	0.43	35	710	34	10	<20	39	0.27	<10	116	<10	17	23
18	X45085	85	<0.2	7.74	20	860	<5	0.39	3	18	212	353	3.51	2.51	30	0.81	189	2	0.83	33	700	28	10	<20	62	0.33	<10	117	<10	17	22
19	X45086	95	<0.2	7.00	10	910	<5	0.35	4	19	349	720	4.33	2.30	40	0.99	194	1	0.83	35	670	32	15	<20	55	0.30	<10	115	<10	21	29
20	X45088	440	0.2	7.21	10	1020	<5	0.64	3	21	153	168	4.61	2.48	30	1.22	158	<1	1.54	44	850	28	5	<20	125	0.32	<10	142	<10	14	22
21	X45089	60	<0.2	6.81	10	775	<5	0.75	3	21	148	171	3.93	2.36	30	1.06	149	1	1.74	43	790	28	<5	<20	165	0.32	<10	116	<10	13	24
22	X45090	290	<0.2	5.89	30	960	<5	0.28	3	16	213	210	3.06	2.71	20	0.34	144	1	1.32	29	470	26	5	<20	135	0.11	<10	71	<10	12	19
23	X45091	85	<0.2	5.99	115	355	<5	0.23	2	18	178	2667	3.13	2.26	40	0.29	66	2	0.47	43	730	32	45	<20	31	0.22	<10	111	<10	17	14
24	X45092	105	0.2	6.54	70	650	<5	0.30	3	17	217	1410	3.41	2.94	30	0.47	76	2	0.75	41	850	28	20	<20	50	0.18	<10	116	<10	13	16
25	X45093	* >1000	3.6	6.38	20	755	30	0.54	4	19	142	2133	4.10	2.67	20	1.13	130	<1	1.84	31	600	30	10	<20	114	0.19	<10	122	<10	13	22

* Based on 120g

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X45094	120	<0.2	6.31	10	590	<5	0.59	3	15	123	304	3.90	2.11	<10	1.31	115	<1	2.61	22	450	28	<5	<20	149	0.25	<10	117	<10	7	18
27	X45095	55	<0.2	5.95	5	1145	<5	0.29	2	5	134	172	1.68	2.69	<10	0.50	85	1	2.72	18	200	32	<5	<20	211	0.09	<10	43	<10	4	11
28	X45096	305	<0.2	7.25	5	725	<5	0.81	3	17	141	380	5.24	2.62	20	1.82	158	2	2.40	27	800	30	<5	<20	162	0.28	<10	137	<10	15	21
29	X45097	* 630	<0.2	6.32	50	260	<5	0.82	4	18	118	291	4.81	1.96	<10	1.92	235	<1	2.66	22	590	44	<5	<20	146	0.28	<10	134	<10	8	93
30	X45098	350	<0.2	7.32	30	585	<5	1.37	3	20	210	129	4.70	2.13	10	1.88	385	<1	2.78	27	470	38	5	<20	214	0.28	<10	111	<10	13	49
31	X45099	70	<0.2	6.74	25	1010	<5	0.51	3	11	182	100	3.74	2.40	<10	1.35	261	<1	2.56	21	330	28	5	<20	174	0.19	<10	71	<10	8	20
32	X45100	120	0.2	7.46	5	395	<5	0.97	3	17	202	137	4.48	1.99	10	2.37	188	<1	3.07	26	560	30	<5	<20	166	0.32	<10	126	<10	9	21
33	X45101	75	<0.2	6.60	10	595	<5	0.38	3	16	141	493	5.36	2.97	<10	1.68	175	<1	2.66	24	530	26	<5	<20	97	0.21	<10	121	<10	5	28
34	X45102	80	<0.2	6.25	15	2855	40	0.28	2	7	135	148	1.78	3.74	60	0.16	101	16	2.61	16	210	46	<5	<20	193	0.07	<10	15	<10	7	23
QC DATA:																															
Repeat:																															
1	X45068		0.8	8.13	70	4515	10	0.06	1	1	100	116	1.07	3.35	90	0.10	16	8	0.50	24	210	34	35	<20	102	0.05	<10	10	<10	4	3
10	X45077	375	0.6	7.21	155	1615	20	0.17	2	8	171	2831	1.31	4.18	20	0.12	21	4	0.48	36	720	34	50	<20	119	0.08	<10	43	<10	10	27
19	X45086	115	0.2	6.96	15	920	<5	0.35	4	19	369	735	4.48	2.39	40	0.99	210	<1	0.88	35	660	32	15	<20	57	0.32	<10	124	<10	22	29
Resplit:																															
1	X45068	>1000	0.6	8.05	85	4445	10	0.07	2	1	107	123	1.01	3.42	90	0.11	13	9	0.52	26	220	36	40	<20	100	0.04	<10	9	<10	4	2
Standard:																															
Stsd3			0.4	5.90	25	1435	<5	2.48	4	18	76	45	4.20	1.48	40	1.25	2623	6	1.30	34	1780	60	<5	<20	243	0.43	<10	126	<10	30	198
SF30		870																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

* Based on 120g

NM/
df/1_TD8066s
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer