Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8054

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

20-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR036
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
18	X45015		1.53	0.045
19	X45016 Dup		1.60	0.047
28	X45025		5.15	0.150
29	X45026		5.10	0.149
35	X45032	*	1.16	0.034

QC DATA:

Repeats:

29	X45026	5.05	0.147

Standard:

OXJ64	2.40	0.070

* Based on 90g

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

20-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8054
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR036
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R233176	10	0.2	8.27	<5	650	<5	3.20	5	71	68	436	>10	2.98	<10	5.70	1500	<1	2.13	35	1420	92	<5	<20	244	0.93	<10	448	<10	27	93
2	8R233177	5	0.2	8.82	<5	1305	<5	2.16	3	28	108	273	4.18	2.47	30	1.33	199	<1	4.59	20	1850	70	<5	<20	497	0.31	<10	122	<10	12	22
3	8R233178	5	<0.2	9.34	5	935	<5	4.80	3	33	113	272	5.24	1.57	30	1.73	430	<1	3.29	22	2570	78	<5	<20	826	0.38	<10	135	<10	17	36
4	X45001	170	0.6	6.65	185	580	5	0.16	4	15	120	938	9.78	1.78	10	0.18	36	<1	0.54	18	710	56	70	<20	45	0.38	<10	237	<10	6	23
5	X45002	105	0.6	9.31	165	620	<5	0.17	4	31	71	831	9.43	1.63	<10	0.21	144	<1	0.68	29	1000	74	35	20	44	0.43	<10	317	<10	10	46
6	X45003	80	0.4	7.31	140	1205	<5	0.09	3	19	69	430	8.04	2.40	20	0.08	104	<1	0.59	17	770	58	40	20	57	0.44	<10	174	<10	12	23
7	X45004	560	0.8	7.82	90	1020	25	0.09	4	22	74	520	9.23	2.06	10	0.14	277	<1	0.59	19	710	62	65	20	42	0.39	<10	183	<10	12	21
8	X45005	275	1.6	7.04	215	800	30	0.08	3	14	127	267	6.08	2.30	10	0.17	197	<1	0.56	17	290	56	145	<20	38	0.17	<10	101	<10	8	19
9	X45006	320	0.6	8.75	200	515	15	0.09	4	21	59	427	9.67	1.56	10	0.13	372	<1	0.61	20	430	68	95	<20	29	0.22	<10	97	<10	10	36
10	X45007	100	0.9	7.63	30	1100	5	0.08	3	14	110	183	5.93	2.80	20	0.13	296	<1	0.58	18	390	62	35	<20	56	0.13	<10	45	<10	12	25
11	X45008	170	1.2	7.82	65	900	<5	0.07	4	23	106	274	>10	2.69	20	0.20	306	<1	0.63	20	700	64	60	<20	46	0.16	<10	145	<10	8	28
12	X45009	390	<0.2	7.06	45	1000	10	0.07	3	6	129	173	5.37	3.02	30	0.20	97	1	0.57	16	260	60	35	<20	42	0.07	<10	54	<10	6	22
13	X45010	260	0.4	7.34	70	1435	10	0.07	3	7	168	181	5.54	3.54	20	0.13	160	3	0.62	17	260	68	35	<20	59	0.09	<10	61	<10	5	21
14	X45011	65	0.4	5.35	150	1355	5	0.06	2	3	154	118	3.16	3.22	20	0.07	49	4	0.47	13	110	52	35	<20	57	0.02	<10	11	<10	5	12
15	X45012	365	0.4	5.15	270	1435	5	0.06	2	3	176	141	3.34	3.24	20	0.12	35	4	0.47	13	170	48	75	<20	59	0.02	<10	22	<10	5	9
16	X45013	170	0.6	8.14	605	1160	35	0.09	4	19	246	354	8.32	3.90	20	0.44	254	<1	0.64	24	610	64	110	40	53	0.28	<10	243	<10	12	31
17	X45014	110	0.4	6.29	190	745	5	0.09	7	63	53	460	>10	1.21	<10	0.11	904	<1	0.73	27	740	66	70	120	26	1.07	<10	795	20	20	60
18	X45015	>1000	3.6	4.50	>10000	140	70	0.06	3	7	178	3833	8.85	2.41	20	0.24	46	36	0.40	13	530	74	295	80	208	0.15	<10	187	<10	5	10
19	X45016 Dup	>1000	3.4	4.70	>10000	140	70	0.07	3	7	164	3836	8.56	2.41	20	0.24	45	39	0.40	12	530	74	300	80	198	0.15	<10	186	<10	5	9
20	X45017	80	0.8	6.43	400	1625	<5	0.06	2	5	111	146	2.94	4.23	20	0.39	74	5	0.54	15	430	54	185	20	74	0.07	<10	58	<10	7	22
21	X45018	175	0.2	6.16	350	1065	5	0.07	2	5	110	208	4.73	3.59	20	0.33	95	4	0.54	16	990	56	85	<20	62	0.07	<10	52	<10	8	35
22	X45019	60	0.2	6.74	110	595	10	0.06	2	5	106	79	2.99	3.01	30	0.40	119	3	0.51	15	410	66	110	<20	21	0.10	<10	52	<10	8	14
23	X45020 Dup	75	0.4	6.60	110	625	10	0.06	2	5	108	78	2.94	2.89	20	0.39	118	3	0.49	15	430	62	105	<20	22	0.09	<10	50	<10	7	14
24	X45021	65	0.6	6.11	170	1075	10	0.05	2	4	105	123	2.28	3.44	20	0.36	57	8	0.49	14	420	92	165	<20	43	0.09	<10	45	<10	7	16
25	X45022	110	0.6	6.57	1030	1995	10	0.07	2	4	146	240	2.62	5.03	30	0.24	28	12	0.57	16	750	70	185	<20	141	0.07	<10	49	<10	8	13

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X45023	190	0.4	5.10	2070	850	20	0.06	2	4	113	130	4.99	3.59	30	0.22	14	4	0.44	12	900	52	155	<20	109	0.09	<10	55	<10	8	4
27	X45024	130	0.6	8.05	165	765	10	0.08	6	24	84	1200	>10	1.12	<10	0.11	302	<1	0.66	26	1320	70	45	20	19	0.27	<10	198	10	10	24
28	X45025	>1000	3.2	9.14	90	830	90	0.08	5	15	97	1045	9.84	2.81	10	0.30	86	<1	0.74	29	1310	78	45	<20	41	0.32	<10	221	<10	8	15
29	X45026	>1000	13.2	4.36	130	400	115	0.08	4	9	135	229	9.66	2.43	10	0.15	64	4	0.45	13	280	44	70	40	51	0.17	<10	54	<10	8	16
30	X45027	615	0.2	7.83	5	145	<5	3.26	3	45	80	26	3.67	3.31	20	2.16	558	2	4.71	106	1310	98	<5	<20	316	0.53	<10	82	<10	9	50
31	X45028	305	2.2	6.80	120	350	45	0.07	6	7	47	241	>10	2.63	30	0.23	30	<1	0.64	18	830	62	75	<20	32	0.05	<10	71	<10	5	18
32	X45029	150	0.8	8.03	40	2645	10	0.08	4	13	108	492	9.87	3.19	50	0.19	140	4	0.75	25	1160	70	25	<20	115	0.06	<10	95	<10	8	27
33	X45030	<5	0.2	6.32	20	555	<5	0.50	2	8	153	27	1.83	4.33	40	0.24	256	5	3.78	18	280	50	<5	<20	132	0.25	<10	26	<10	20	36
34	X45031	105	0.4	7.84	35	1585	15	0.07	3	16	197	404	5.94	3.34	30	0.84	178	1	0.64	29	780	60	10	<20	78	0.34	<10	100	<10	12	44
35	X45032	>1000	0.6	5.21	35	2490	20	0.05	3	12	267	472	6.61	2.09	20	0.18	203	5	0.45	27	850	44	20	<20	57	0.17	<10	86	<10	10	34
QC DATA:																															
Repeat:																															
1	8R233176	15	0.2	8.19	<5	685	<5	3.29	5	76	69	449	>10	3.02	<10	5.90	1549	<1	2.19	39	1470	88	<5	<20	248	0.92	<10	458	<10	29	88
7	X45004	590																													
10	X45007	125	1.1	7.58	45	1100	5	0.08	3	14	112	187	6.10	2.87	20	0.13	306	<1	0.60	18	400	64	35	<20	56	0.14	<10	46	<10	11	24
19	X45016 Dup	>1000	3.4	4.54	>10000	135	70	0.07	3	7	169	3807	8.68	2.42	20	0.24	46	38	0.41	12	520	74	295	80	195	0.16	<10	187	<10	5	11
31	X45028	310																													
Resplit:																															
1	8R233176	20	<0.2	8.25	<5	620	<5	3.19	5	73	66	423	>10	2.90	<10	5.85	1543	<1	2.12	38	1450	82	<5	<20	229	0.87	<10	431	<10	28	82
Standard:																															
Stsd3			0.4	5.89	25	1435	<5	2.46	4	28	67	43	4.25	1.48	30	1.32	2711	7	1.29	47	1720	68	<5	<20	227	0.40	<10	131	<10	33	201
OXE74		620																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8054RS
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer