Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8075

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

23-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR058
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
15	X46015			1569	45.76
17	X46017	1.52	0.044		
18	X46018	1.22	0.036		
31	X46032	1.05	0.031		
QC DATA:					
Repeat:					
15	X46015			1604	46.78
17	X46017	1.58	0.046		
Standard:					
OXI67		1.84	0.054		
Pb104				104	3.03
Kc1a				1679	48.97

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

21-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8075
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR058
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X46001	400	1.8	5.93	10	215	<5	0.96	5	41	42	1078	>10	2.73	<10	3.22	382	<1	1.89	28	970	86	<5	<20	112	0.80	<10	355	10	14	43
2	X46002	140	0.8	6.13	15	545	<5	0.78	3	14	99	495	4.40	1.86	20	0.80	167	<1	3.80	21	740	68	<5	<20	331	0.13	<10	68	<10	11	16
3	X46003	135	1.8	5.93	25	195	<5	0.89	5	37	44	1023	9.67	2.13	<10	2.69	474	<1	1.76	26	930	78	10	<20	89	0.79	<10	296	<10	16	38
4	X46004	35	0.6	5.64	10	570	<5	0.40	2	14	121	343	3.74	1.46	<10	0.89	218	<1	4.04	20	290	64	<5	<20	133	0.22	<10	83	<10	10	23
5	X46005	435	1.0	6.80	20	385	<5	1.60	5	39	55	735	7.36	1.57	<10	1.68	553	<1	2.14	29	1370	76	10	20	122	0.95	<10	329	10	12	56
6	X46006	175	0.6	6.38	10	270	<5	2.25	5	34	43	498	8.69	1.31	<10	2.40	1120	<1	2.41	31	1010	74	5	40	138	0.86	<10	310	10	20	81
7	X46007	300	1.0	6.92	15	450	<5	2.38	5	29	26	556	7.77	1.60	<10	2.73	737	<1	2.25	31	1010	80	5	40	134	0.94	<10	329	<10	20	59
8	X46008 Dup	285	0.8	7.15	15	480	<5	2.37	5	30	30	535	7.70	1.65	<10	2.79	724	<1	2.28	31	1030	84	5	40	137	0.94	<10	330	<10	20	59
9	X46009	175	1.2	6.03	30	135	<5	0.76	6	38	61	1091	>10	1.65	<10	2.33	335	<1	1.74	29	920	74	15	20	63	0.68	<10	262	10	12	29
10	X46010	45	0.4	7.26	65	200	<5	0.60	4	25	86	236	6.43	1.61	10	1.88	330	<1	1.95	31	800	76	15	20	65	0.62	<10	223	<10	15	36
11	X46011	210	0.2	8.25	90	115	<5	0.71	6	54	57	638	8.97	1.11	10	0.92	261	<1	0.59	39	1500	80	45	40	26	0.86	<10	364	<10	20	19
12	X46012	<5	<0.2	6.71	15	515	<5	0.48	2	6	140	20	1.94	4.20	40	0.18	260	4	3.79	18	230	66	<5	<20	138	0.23	<10	26	<10	18	34
13	X46013	45	0.4	8.31	155	115	<5	0.82	7	61	49	520	>10	0.92	10	0.93	693	<1	0.60	41	1330	84	60	40	27	0.81	<10	331	10	22	52
14	X46014	35	<0.2	8.26	65	260	<5	0.55	3	28	96	173	3.66	0.72	20	0.56	225	<1	0.54	28	1120	68	20	<20	28	0.53	<10	95	<10	29	22
15	X46015	405	>30	6.89	40	250	15	0.37	3	21	129	2997	4.18	1.49	20	0.26	315	647	0.55	248	720	190	50	<20	43	0.19	<10	71	70	15	66
16	X46016	40	1.0	6.20	20	1245	35	0.19	3	24	120	511	4.08	2.50	40	0.26	670	<1	0.57	31	210	108	25	<20	66	0.08	<10	31	<10	15	136
17	X46017	>1000	3.6	7.08	55	180	635	0.33	6	37	184	2264	7.16	3.11	20	0.70	502	<1	0.64	54	500	292	50	<20	74	0.15	<10	129	<10	9	152
18	X46018	>1000	2.6	6.00	40	45	35	0.20	5	35	152	1132	5.68	1.75	30	0.38	460	<1	0.49	40	270	122	45	<20	53	0.08	<10	54	<10	10	112
19	X46019	40	<0.2	5.77	15	785	10	0.13	3	14	114	191	3.98	1.60	30	0.18	541	<1	0.47	21	80	66	25	<20	56	0.03	<10	11	<10	10	57
20	X46020	65	0.2	6.32	20	545	<5	0.17	3	11	96	183	3.80	1.26	30	0.20	489	1	0.47	20	260	62	35	<20	31	0.05	<10	13	<10	13	28
21	X46021	10	<0.2	5.61	10	765	<5	0.07	2	3	117	43	0.80	2.35	30	0.17	115	3	0.46	18	90	56	10	<20	25	0.04	<10	8	<10	7	28
22	X46022	10	<0.2	5.91	10	1275	<5	0.08	2	3	138	36	0.93	2.54	30	0.12	157	2	0.48	20	100	60	10	<20	41	0.02	<10	8	<10	8	29
23	X46023	50	<0.2	6.74	40	1075	<5	0.24	5	20	107	223	4.14	3.25	40	0.20	577	3	0.60	35	590	72	15	<20	99	0.13	<10	34	<10	18	41
24	X46024	75	0.2	6.34	55	555	<5	0.26	5	20	111	280	4.63	2.97	30	0.22	567	4	0.60	36	620	74	20	<20	98	0.12	<10	34	<10	13	40
25	X46025	80	0.6	6.59	25	1815	<5	0.27	4	14	110	451	4.62	3.52	30	0.22	670	3	0.66	32	660	82	10	<20	119	0.12	<10	36	<10	14	53

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X46027	170 700	0.4	6.44	25	1740	15	0.29	5	15	109	365	3.96	2.81	40	0.27	539	<1	0.61	31	650	110	15	<20	85	0.15	<10	38	<10	15	124
27	X46028	140	<0.2	7.84	30	370	<5	0.47	5	28	177	436	7.66	1.92	30	0.73	613	<1	0.66	56	640	90	15	<20	46	0.44	<10	149	10	18	62
28	X46029	65	0.6	6.43	40	2620	<5	0.28	4	12	132	363	2.12	3.95	30	0.33	128	3	0.71	35	640	86	20	<20	128	0.22	<10	51	<10	16	33
29	X46030	180	2.2	8.22	35	650	25	0.52	5	31	177	1407	7.63	2.66	20	1.44	431	<1	1.29	60	720	108	10	<20	66	0.46	<10	171	<10	13	54
30	X46031	95	0.8	5.88	35	520	<5	0.73	3	15	173	652	3.67	1.74	50	0.65	255	2	2.42	27	190	64	15	<20	80	0.09	<10	24	<10	12	29
31	X46032	>1000	3.8	7.49	30	1490	<5	0.98	6	17	111	3205	4.40	4.00	30	0.79	349	269	1.03	21	720	162	30	<20	149	0.28	<10	82	<10	9	190
32	X46033	40	0.2	5.93	20	1130	<5	0.57	3	14	211	209	3.83	2.28	20	0.54	401	2	1.71	32	220	60	15	<20	90	0.10	<10	28	<10	9	43
33	X46034	630	0.2	6.35	20	1530	10	0.27	3	13	126	302	3.40	2.95	30	0.22	306	4	0.66	26	610	64	15	<20	128	0.14	<10	37	<10	16	73
34	X46035	75	0.2	6.26	35	1065	<5	0.29	2	13	244	140	2.99	1.93	20	0.47	371	2	1.37	27	200	58	15	<20	70	0.09	<10	22	<10	10	47
QC DATA:																															
Repeat:																															
1	X46001	370	1.6	6.06	10	230	<5	0.99	5	42	43	1112	>10	2.65	10	3.33	400	<1	1.98	30	980	84	<5	<20	115	0.82	<10	360	10	14	41
5	X46005	470																													
10	X46010	60	0.4	7.52	75	195	<5	0.60	5	26	80	228	6.27	1.53	20	2.03	324	<1	1.88	35	840	82	15	20	63	0.59	<10	214	<10	14	35
19	X46019	30	<0.2	5.62	15	785	5	0.13	3	14	121	187	3.95	1.62	30	0.17	532	<1	0.55	27	80	72	25	<20	55	0.03	<10	11	<10	10	55
33	X46034	575																													
Resplit:																															
1	X46001	360	1.8	6.55	10	250	<5	1.02	7	47	44	1081	>10	2.44	<10	3.58	394	<1	1.92	36	1040	92	<5	<20	121	0.77	<10	372	<10	14	42
Standard:																															
Stsd3			0.4	5.84	25	1400	<5	2.49	4	22	72	36	4.09	1.17	30	1.35	2680	6	1.28	48	1790	68	<5	<20	243	0.44	<10	131	<10	32	196
SF30		825																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8075S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer