Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8041

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

10-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR027
Submitted by: Roger Hulsein

ET #.	Tag #	Au (g/t)	Au (oz/t)
34	8R231454	1.44	0.042
QC DATA:			
Repeat:			
34	8R231454	1.35	0.039
Standard:			
Oxi67		1.82	0.053

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

7-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8041
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR027
Submitted by: Roger Hulsein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R231421	235	0.6	7.87	35	790	<5	0.66	2	14	202	453	3.18	4.21	30	0.84	156	3	2.62	26	680	58	<5	<20	168	0.18	<10	127	<10	12	24
2	8R231422	135	<0.2	7.70	15	990	<5	0.82	2	31	241	239	2.79	3.97	30	0.83	158	2	2.72	49	770	54	<5	<20	203	0.20	<10	130	<10	13	44
3	8R231423	75	0.2	7.60	40	855	<5	1.01	3	24	141	376	3.44	3.22	20	0.98	211	3	3.08	31	620	56	<5	<20	223	0.18	<10	117	<10	11	44
4	8R231424	150	0.2	7.60	15	1000	<5	0.92	2	26	216	240	2.68	3.69	20	0.87	91	4	3.21	41	680	54	<5	<20	199	0.18	<10	120	<10	13	37
5	8R231425	160	0.2	8.25	155	930	15	0.77	3	18	194	359	4.20	3.95	30	0.89	108	2	2.19	31	770	58	<5	<20	145	0.21	<10	147	<10	13	38
6	8R231426 Dup	160	<0.2	8.30	130	965	20	0.75	3	18	208	374	4.04	4.04	30	0.91	109	1	2.15	31	770	58	<5	<20	144	0.21	<10	149	<10	13	36
7	8R231427	160	<0.2	8.10	170	825	<5	0.67	3	13	190	693	3.92	3.80	30	0.96	114	1	2.37	28	660	58	<5	<20	137	0.20	<10	144	<10	16	39
8	8R231428	45	<0.2	8.09	105	1120	<5	0.76	3	25	230	463	3.78	4.10	30	0.95	132	2	1.99	49	760	56	<5	<20	137	0.22	<10	140	<10	16	57
9	8R231429	55	<0.2	8.06	25	1070	<5	1.17	3	20	178	317	3.86	3.32	20	1.31	205	1	2.68	39	660	60	<5	<20	159	0.21	<10	141	<10	13	33
10	8R231430	70	0.4	8.06	60	820	35	0.90	3	22	254	720	4.55	3.60	20	1.36	169	<1	2.61	35	670	62	<5	<20	162	0.20	<10	159	<10	12	39
11	8R231431	20	0.2	7.38	35	1460	20	0.12	2	8	106	199	3.68	4.71	20	0.30	37	2	2.44	19	810	56	<5	<20	281	0.03	<10	42	<10	9	44
12	8R231432	95	0.2	7.81	65	1545	80	0.12	2	5	107	237	2.84	4.69	30	0.37	35	2	2.24	20	730	62	<5	<20	244	0.04	<10	42	<10	10	30
13	8R231433	<5	0.2	7.25	15	510	<5	0.49	2	6	130	20	1.78	5.19	30	0.23	224	4	3.58	14	270	62	<5	<20	148	0.18	<10	22	<10	17	34
14	8R231434	105	<0.2	7.65	45	840	<5	0.90	3	13	129	340	4.35	3.75	20	1.35	139	1	3.20	25	700	58	<5	<20	179	0.17	<10	135	<10	11	33
15	8R231435	110	<0.2	7.74	90	1060	<5	0.74	3	22	218	328	3.59	3.82	30	1.04	135	3	2.46	42	780	56	<5	<20	145	0.19	<10	136	<10	13	39
16	8R231436	50	0.2	7.80	235	1305	<5	0.60	3	17	215	568	3.34	3.86	20	0.83	112	2	2.41	32	630	56	<5	<20	157	0.18	<10	114	<10	11	33
17	8R231437	605	<0.2	8.43	<5	115	<5	2.71	2	28	69	23	3.47	4.42	10	1.88	477	1	4.24	81	1180	86	<5	<20	338	0.56	<10	68	<10	7	42
18	8R231438	65	<0.2	7.74	485	1005	<5	0.60	3	17	226	427	4.11	3.79	30	0.74	138	<1	1.56	33	680	76	<5	<20	124	0.20	<10	129	<10	11	61
19	8R231439	75	<0.2	8.12	50	1205	<5	0.95	3	28	217	198	3.54	4.14	30	1.05	176	2	2.37	53	880	56	<5	<20	157	0.23	<10	136	<10	13	29
20	8R231440	55	<0.2	6.67	20	1020	<5	0.89	3	19	174	330	5.88	1.85	20	1.08	203	15	2.80	15	520	54	<5	<20	128	0.27	<10	102	<10	17	25
21	8R231441	65	0.2	7.43	25	365	<5	2.59	4	38	96	869	8.32	2.17	10	1.70	578	<1	3.16	27	700	64	<5	<20	158	0.42	<10	306	<10	33	51
22	8R231442	30	<0.2	6.03	20	210	<5	0.45	2	14	145	346	4.62	1.11	10	0.58	117	2	3.65	8	340	48	<5	<20	92	0.15	<10	31	<10	18	18
23	8R231443	240	<0.2	6.79	40	420	<5	1.28	4	34	109	451	6.84	2.27	10	1.89	467	<1	3.64	30	380	62	<5	<20	149	0.23	<10	184	<10	24	64
24	8R231444	* 395	0.2	7.10	65	1170	<5	1.57	4	35	84	624	7.26	2.36	<10	1.96	629	<1	3.70	28	530	62	<5	<20	132	0.34	<10	269	<10	27	62
25	8R231445	25	<0.2	6.03	60	520	<5	0.60	3	22	158	688	3.18	0.83	<10	0.57	118	<1	4.62	23	290	50	<5	<20	105	0.11	<10	31	<10	20	24

* Based on 120g

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R231446	25	<0.2	7.63	35	1150	<5	2.42	5	53	66	331	7.96	1.86	<10	2.48	1859	<1	4.55	39	600	70	<5	<20	142	0.37	<10	308	<10	37	89
27	8R231447	85	0.4	8.02	785	265	<5	0.84	5	80	124	1041	>10	1.21	10	0.58	774	<1	3.35	73	600	70	5	<20	144	0.38	<10	314	10	42	174
28	8R231448	500	0.5	7.33	60	400	15	2.12	4	34	93	477	6.54	2.18	<10	2.48	853	<1	4.50	34	480	66	<5	<20	146	0.31	<10	240	<10	22	61
29	8R231449	360	1.0	7.35	60	365	30	2.25	4	37	98	895	6.68	2.07	<10	2.50	903	<1	4.52	34	490	66	<5	<20	135	0.31	<10	250	<10	24	70
30	8R231450	200	0.8	5.62	195	640	<5	0.64	3	32	163	584	4.55	2.03	<10	1.01	113	<1	3.59	33	1120	64	5	<20	88	0.12	<10	70	<10	12	35
31	8R231451	120	1.0	6.25	80	240	<5	0.63	4	43	69	1398	8.47	2.55	<10	1.94	196	<1	3.52	28	470	66	<5	<20	91	0.31	<10	285	<10	8	43
32	8R231452	535	0.8	7.36	50	3005	10	0.36	2	10	124	361	1.97	2.60	50	0.28	40	<1	3.92	17	300	64	<5	<20	258	0.05	<10	17	<10	8	14
33	8R231453	275	0.8	6.42	20	1375	<5	0.50	2	13	157	541	3.22	3.04	10	1.00	91	4	3.94	19	450	52	<5	<20	104	0.11	<10	69	<10	7	21
34	8R231454	>1000	1.8	6.53	15	455	20	0.10	2	15	173	1613	3.01	2.80	20	0.21	37	15	0.88	17	220	62	<5	<20	137	0.03	<10	21	<10	7	19
35	8R231455	* 625	0.6	6.40	15	3195	10	0.17	2	4	151	303	1.25	4.60	<10	0.19	34	2	1.86	15	180	60	<5	<20	355	0.02	<10	16	<10	3	16
QC DATA:																															
Repeat:																															
1	8R231421	195	0.4	7.88	35	755	<5	0.62	2	13	196	465	3.08	4.35	20	0.84	149	3	2.63	25	670	54	<5	<20	161	0.18	<10	135	<10	12	25
10	8R231430	90	0.2	8.02	60	810	35	0.89	3	22	253	716	4.53	3.60	20	1.36	168	<1	2.58	35	670	62	<5	<20	158	0.20	<10	158	<10	11	38
19	8R231439	80	<0.2	7.98	55	1185	<5	0.94	3	28	212	195	3.49	4.10	30	1.04	173	2	2.38	55	870	60	<5	<20	154	0.23	<10	128	<10	13	29
32	8R231452	485																													
Resplit:																															
1	8R231421	215	0.6	7.79	35	775	<5	0.64	2	14	198	457	3.18	3.88	30	0.83	154	3	2.61	27	680	58	<5	<20	165	0.18	<10	134	<10	13	24
Standard:																															
Stsd3			0.4	5.85	25	1475	<5	2.43	3	18	79	43	3.96	1.75	40	1.32	2487	5	1.22	33	1560	72	<5	<20	226	0.40	<10	127	<10	34	193
OXE74		615																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

* Based on 120g

NM/nw
df/2_TD8038S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer