Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8066

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

22-Jul-09

Attn: Graeme Hopkins

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR045
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
6	8R232771	2.76	0.080
12	8R232777	4.91	0.143
27	8R232792	1.69	0.049
29	8R232794	1.03	0.030
31	8R232796	3.02	0.088
32	8R232797	1.29	0.038

QC DATA:

Repeats:

6	8R232771	2.37	0.069
31	8R232796	3.06	0.089

Standard:

OXJ64	2.30	0.067
SK43	4.03	0.118

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

17-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8066
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR045
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R232766	110	<0.2	9.86	5	185	<5	5.50	4	31	77	247	5.30	1.30	10	2.94	802	<1	2.90	38	1030	44	<5	<20	331	0.67	<10	225	<10	19	56
2	8R232767	180	<0.2	9.39	10	165	<5	4.31	4	31	65	794	6.51	1.73	20	2.20	553	<1	3.51	33	1750	40	<5	<20	355	0.92	<10	291	<10	27	41
3	8R232768	280	<0.2	8.97	15	135	<5	2.87	4	35	59	702	7.57	1.69	10	2.07	428	<1	2.98	35	980	38	<5	<20	295	0.68	<10	245	<10	23	68
4	8R232769	545	0.4	6.61	20	5335	<5	0.47	2	8	114	173	2.16	3.06	30	0.14	75	<1	3.22	16	260	32	<5	<20	285	0.14	<10	22	<10	5	24
5	8R232770	650	1.6	8.83	10	230	<5	1.83	4	24	92	802	5.69	2.21	20	1.94	238	<1	2.97	34	1110	36	<5	<20	280	0.62	<10	209	<10	12	57
6	8R232771	>1000	2.8	8.64	105	170	<5	1.80	8	73	133	3823	8.64	1.81	10	2.02	1526	<1	2.00	83	1270	38	10	<20	133	0.60	<10	217	<10	41	138
7	8R232772	555	1.4	>10	70	455	<5	0.27	4	13	59	565	6.36	2.42	20	0.58	87	<1	0.63	30	1650	46	35	<20	104	0.74	<10	294	10	8	38
8	8R232773	630	2.4	7.67	345	660	70	0.08	3	7	123	251	5.51	2.83	10	0.49	88	6	0.56	16	740	30	75	20	96	0.19	<10	176	<10	5	56
9	8R232774	580	1.0	8.65	275	120	20	0.11	6	18	55	1261	>10	1.29	10	0.28	185	<1	0.57	26	1170	38	125	<20	25	0.36	<10	205	10	10	118
10	8R232775	200	0.6	>10	35	625	<5	1.20	4	15	92	3205	4.68	1.41	10	1.32	98	<1	0.54	40	1210	40	25	<20	27	0.64	<10	238	<10	18	31
11	8R232776	235	<0.2	8.15	40	1020	35	0.20	3	5	133	296	3.74	3.47	20	1.22	68	4	1.31	17	680	30	10	<20	91	0.25	<10	147	<10	7	16
12	8R232777	>1000	3.0	5.24	15	165	<5	0.99	2	8	28	48	2.52	4.81	<10	0.13	151	370	0.63	32	490	162	10	<20	710	0.06	<10	36	<10	4	288
13	8R232778	65	<0.2	7.56	25	1115	<5	0.22	2	4	165	221	2.62	2.85	20	0.69	44	2	1.62	15	670	28	10	<20	126	0.20	<10	122	<10	9	17
14	8R232779	150	<0.2	7.16	40	880	<5	0.06	2	4	197	228	3.59	2.90	20	0.33	44	3	0.45	14	850	40	15	<20	57	0.11	<10	126	<10	6	29
15	8R232780	185	0.2	6.85	75	725	5	0.06	2	6	73	222	2.91	3.10	30	0.27	49	2	0.39	14	860	60	30	<20	81	0.07	<10	46	<10	12	37
16	8R232781	305	0.2	7.12	35	975	<5	0.06	2	2	77	212	2.62	3.20	20	0.24	25	2	0.39	12	660	32	25	<20	76	0.07	<10	44	<10	8	18
17	8R232782	105	0.2	7.31	35	805	<5	0.05	3	4	183	291	4.40	2.58	30	0.23	44	<1	0.41	14	990	28	15	<20	50	0.09	<10	121	<10	4	27
18	8R232783	85	0.8	7.22	70	1695	<5	0.06	2	7	83	223	3.59	4.11	30	0.18	56	4	0.47	14	850	28	20	<20	154	0.13	<10	57	<10	8	45
19	8R232784	95	0.8	6.72	190	1345	<5	0.06	3	13	77	144	4.65	3.33	30	0.17	96	3	0.43	17	750	28	30	<20	156	0.12	<10	51	<10	9	100
20	8R232785	290	0.6	6.78	220	1455	<5	0.06	3	18	73	179	4.78	3.29	30	0.16	118	5	0.43	23	950	28	35	<20	146	0.12	<10	49	<10	11	143
21	8R232786	295	<0.2	7.19	165	1385	25	0.05	3	14	83	201	3.92	3.18	30	0.19	97	6	0.44	20	760	28	25	<20	120	0.08	<10	43	<10	9	83
22	8R232787	100	<0.2	7.33	35	850	<5	0.05	3	3	168	306	4.38	2.66	30	0.23	39	1	0.43	13	990	28	15	<20	55	0.11	<10	127	<10	5	24
23	8R232788	370	0.6	6.55	280	1120	<5	0.05	2	14	100	168	4.03	3.03	30	0.24	107	4	0.44	19	680	28	30	<20	96	0.09	<10	46	<10	10	85
24	8R232789	195	0.2	6.40	235	1395	<5	0.06	3	14	92	182	4.78	2.84	30	0.19	103	2	0.46	21	770	28	25	<20	152	0.07	<10	39	<10	11	148
25	8R232790	55	0.8	6.59	160	1495	<5	0.06	2	8	102	364	2.09	3.57	20	0.17	27	3	0.49	17	530	38	20	<20	153	0.04	<10	21	<10	14	103

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R232791	135	0.6	6.54	320	1190	<5	0.07	3	17	98	1001	4.42	3.48	20	0.18	45	2	0.49	33	670	54	50	<20	139	0.05	<10	29	<10	14	191
27	8R232792	>1000	0.4	6.84	145	1625	55	0.07	3	9	79	345	4.78	2.77	30	0.19	41	2	0.46	19	960	30	25	<20	135	0.09	<10	51	<10	10	142
28	8R232793	<5	<0.2	6.45	15	470	<5	0.48	1	5	147	23	1.86	4.03	30	0.19	248	3	3.33	12	240	50	<5	<20	148	0.21	<10	22	<10	15	35
29	8R232794	>1000	0.4	5.87	110	575	<5	0.08	4	11	114	418	8.39	1.91	20	0.22	150	<1	0.68	15	570	26	30	<20	49	0.12	<10	126	<10	9	35
30	8R232795	705	1.2	6.46	50	480	<5	0.35	4	23	133	1924	4.63	2.08	<10	0.86	123	<1	2.35	22	480	34	15	<20	79	0.19	<10	125	<10	15	26
31	8R232796	>1000	0.4	7.69	40	440	<5	1.57	5	44	82	485	9.28	1.76	<10	2.58	767	<1	3.11	30	720	34	5	<20	147	0.74	<10	315	<10	23	64
32	8R232797	>1000	0.2	6.24	70	235	10	0.58	4	29	188	438	6.34	1.75	<10	1.76	439	<1	2.62	32	350	30	15	<20	78	0.20	<10	112	<10	9	40
33	8R232798	925	0.4	6.03	95	385	<5	0.37	3	23	97	629	5.29	1.93	<10	1.50	143	<1	2.51	18	490	26	10	<20	89	0.34	<10	182	<10	9	27
34	8R232799	625	1.2	6.37	35	245	<5	0.35	4	25	88	1249	6.71	2.25	<10	1.79	166	<1	2.52	21	630	28	10	<20	75	0.36	<10	243	<10	6	35
35	8R232800 Dup	785	1.4	6.26	35	255	<5	0.36	4	25	101	1292	6.97	2.26	<10	1.68	177	<1	2.62	21	610	28	10	<20	80	0.34	<10	237	<10	7	29
QC DATA:																															
Repeat:																															
1	8R232766	90	0.2	>10	5	175	<5	5.32	4	30	72	238	5.17	1.23	10	3.06	810	<1	2.82	38	1030	38	<5	<20	321	0.64	<10	219	<10	16	50
2	8R232767	180																													
5	8R232770	610																													
9	8R232774	560																													
10	8R232775	205	0.8	>10	35	605	<5	1.18	3	14	90	3160	4.63	1.40	10	1.32	98	<1	0.56	40	1200	38	25	<20	27	0.63	<10	236	<10	18	27
19	8R232784	115	0.6	6.94	195	1360	<5	0.06	3	13	76	143	4.52	3.25	30	0.18	94	3	0.44	18	780	28	35	<20	158	0.13	<10	49	<10	9	104
23	8R232788	350																													
34	8R232799	630																													
35	8R232800 Dup	790																													
Resplit:																															
1	8R232766	95	<0.2	9.79	5	175	<5	5.38	4	30	69	235	5.36	1.26	10	2.92	832	<1	2.90	39	1000	40	<5	<20	322	0.63	<10	223	<10	17	52
Standard:																															
Stsd3			0.4	5.91	25	1415	<5	2.51	3	18	75	43	4.18	1.41	40	1.36	2625	6	1.16	33	1810	60	<5	<20	245	0.42	<10	126	<10	33	193
SF30		815																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/ap
df/1_TD8066S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer