Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8056

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

21-Jul-09

Attn: Graeme Hopkins

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR042
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
12	X45044		1.31	0.038
14	X45046		1.38	0.040
16	X45048		1.04	0.030
18	X45050		1.44	0.042
19	X45051	*	2.82	0.082
20	X45052		2.18	0.064
21	X45053 Dup		2.12	0.062
22	X45054	*	2.07	0.060
32	X45064		1.32	0.038
33	X45065	*	4.14	0.121
34	X45066		1.11	0.032
35	X45067		1.84	0.054

* Based on 150g

QC DATA:

Repeat:

12	X45044	1.27	0.037
34	X45066	1.23	0.036

Standard:

OXI67	1.80	0.052
SK43	4.11	0.120

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

16-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8056
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR042
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X45033	40	0.4	4.68	55	1575	<5	0.05	2	9	229	564	6.33	1.96	10	0.12	145	<1	0.31	16	720	34	20	<20	66	0.09	<10	78	<10	8	36
2	X45034	45	0.2	7.19	210	535	<5	0.08	3	10	236	517	7.55	2.81	20	0.52	109	<1	0.50	16	1550	136	20	<20	141	0.16	<10	153	<10	16	61
3	X45035	100	0.6	5.11	345	2295	10	0.05	2	10	246	306	4.16	2.51	10	0.16	99	5	0.34	18	890	78	35	<20	91	0.10	<10	87	<10	12	44
4	X45036	165	1.0	3.61	75	2065	5	0.05	1	15	295	373	4.63	2.08	10	0.13	132	5	0.25	29	1390	27	15	<20	74	0.07	<10	99	<10	20	71
5	X45037	360	0.8	4.01	215	2140	10	0.04	1	6	280	275	2.45	2.34	10	0.13	55	4	0.27	18	670	94	35	<20	74	0.07	<10	64	<10	7	48
6	X45038	75	1.0	3.14	90	695	<5	0.04	<1	5	230	231	2.50	2.10	10	0.14	53	5	0.23	13	750	66	15	<20	75	0.07	<10	66	<10	5	20
7	X45039	95	1.6	8.26	60	620	<5	0.08	2	4	106	330	5.14	3.25	40	0.15	16	2	0.57	22	1120	56	15	<20	86	0.12	<10	46	<10	5	5
8	X45040	60	0.2	7.58	30	805	<5	0.32	2	5	123	367	2.94	2.10	10	0.58	42	<1	2.32	17	490	48	10	<20	95	0.16	<10	52	<10	7	14
9	X45041	35	0.2	9.34	10	1250	<5	0.53	2	17	117	2674	4.03	3.65	30	1.26	91	<1	2.51	34	910	67	5	<20	160	0.32	<10	107	<10	30	28
10	X45042	85	0.2	8.09	10	285	10	0.57	4	26	164	1097	7.55	2.08	30	1.60	371	<1	2.93	49	1160	59	10	<20	103	0.27	<10	157	<10	37	58
11	X45043	105	2.2	7.86	115	225	10	0.34	3	37	76	7005	6.29	4.18	30	0.57	212	<1	2.98	43	560	142	15	<20	133	0.09	<10	87	<10	14	151
12	X45044	>1000	1.0	8.92	10	130	20	1.48	4	38	88	696	7.63	2.06	10	2.10	530	<1	3.07	36	1340	59	5	20	183	0.44	<10	246	<10	20	65
13	X45045	950	0.6	8.82	15	80	10	0.85	3	52	78	324	9.69	1.61	20	2.08	1239	2	2.28	46	1050	54	20	<20	63	0.43	<10	209	<10	41	124
14	X45046	>1000	1.2	8.92	20	240	110	1.66	3	32	106	449	6.54	2.46	20	2.91	516	<1	2.90	41	1390	128	10	<20	185	0.40	<10	196	<10	20	107
15	X45047	230	0.8	7.11	15	1490	55	0.51	2	15	110	377	3.09	4.00	90	0.36	177	9	3.07	18	400	107	5	<20	283	0.13	<10	32	<10	13	17
16	X45048	>1000	3.6	7.46	35	1555	<5	1.02	4	20	106	3324	4.39	4.09	30	0.81	346	282	0.90	22	760	162	30	<20	166	0.33	<10	91	<10	12	176
17	X45049	980	1.8	7.96	10	310	30	0.90	4	41	137	1297	7.34	2.58	30	2.21	451	1	2.64	47	1240	178	5	<20	170	0.26	<10	174	<10	14	155
18	X45050	>1000	0.8	7.27	85	735	15	0.48	2	31	289	563	5.27	2.94	30	1.19	497	5	1.47	44	770	50	10	<20	91	0.22	<10	114	<10	24	47
19	X45051	>1000	0.4	7.67	10	1215	35	0.31	2	24	273	397	4.49	3.11	30	0.88	390	2	0.48	39	750	72	15	<20	44	0.29	<10	145	<10	23	61
20	X45052	>1000	1.0	6.98	130	1345	45	0.21	2	25	260	546	4.34	2.90	30	0.59	269	3	0.66	30	420	56	15	<20	69	0.14	<10	70	<10	24	72
21	X45053 Dup	>1000	0.8	6.67	120	1365	40	0.21	2	23	240	548	4.16	2.99	30	0.57	255	3	0.66	28	420	53	15	<20	70	0.14	<10	72	<10	23	67
22	X45054	>1000	0.8	6.85	45	1245	10	0.33	2	35	230	408	5.32	2.86	30	1.04	523	2	0.51	49	700	45	15	<20	44	0.25	<10	122	<10	29	63
23	X45055	330	<0.2	6.72	20	1155	<5	0.41	2	27	228	163	4.88	2.93	20	1.21	425	2	0.92	40	660	42	5	<20	60	0.30	<10	142	<10	24	40
24	X45056	400	0.2	6.89	35	1155	20	0.48	2	30	216	154	5.55	2.99	30	1.15	533	2	0.91	42	660	45	5	<20	51	0.31	<10	141	<10	30	47
25	X45057	355	0.8	7.25	15	1185	20	0.39	3	29	258	733	5.71	3.37	20	1.60	487	2	0.53	55	830	59	10	<20	33	0.34	<10	158	<10	28	94

ECO TECH LABORATORY LTD. **ICP CERTIFICATE OF ANALYSIS AW 2009-8056** **Bushmaster Exploration**

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X45058	580	0.4	7.87	25	795	<5	0.35	3	26	376	977	5.81	2.71	20	1.84	351	2	0.53	73	980	53	10	<20	21	0.40	<10	193	<10	26	41
27	X45059	200	0.2	6.52	15	1445	<5	0.26	1	8	217	998	1.93	3.68	10	0.43	76	3	1.70	28	310	50	5	<20	144	0.12	<10	55	<10	12	11
28	X45060	5	0.2	6.79	15	500	<5	0.51	1	6	144	27	1.75	4.82	30	0.19	246	4	3.25	11	260	48	<5	<20	126	0.20	<10	24	<10	17	32
29	X45061	* 405	0.4	8.12	25	1100	<5	0.21	2	18	240	1755	3.14	2.90	30	1.04	172	2	0.59	42	780	51	10	<20	36	0.32	<10	149	<10	26	24
30	X45062	170	0.6	1.77	20	475	<5	0.02	<1	5	482	1143	0.93	0.62	10	0.16	71	2	0.09	24	130	8	15	<20	9	0.04	<10	29	<10	6	10
31	X45063 Dup	185	0.6	1.79	20	465	<5	0.02	<1	5	457	1069	0.87	0.60	10	0.16	69	3	0.09	23	130	8	15	<20	8	0.04	<10	28	<10	6	10
32	X45064	>1000	0.4	7.73	40	1555	25	0.08	2	14	255	1962	2.08	3.23	20	0.60	93	2	0.46	40	540	58	15	<20	40	0.29	<10	143	<10	13	21
33	X45065	>1000	0.4	7.84	35	1595	55	0.08	1	8	282	1081	1.12	3.92	20	0.27	39	6	0.48	33	440	59	15	<20	113	0.15	<10	69	<10	11	8
34	X45066	>1000	0.8	8.32	160	1305	5	0.08	1	11	194	1966	1.68	3.48	30	0.32	43	2	0.48	38	670	58	55	<20	50	0.22	<10	140	<10	13	20
35	X45067	>1000	1.4	8.12	120	3080	10	0.07	1	3	161	578	1.15	3.70	70	0.11	20	7	0.53	27	350	61	65	<20	70	0.08	<10	33	<10	6	6
QC DATA:																															
Repeat:																															
1	X45033	35	0.2	4.65	55	1525	<5	0.06	2	9	223	560	6.36	1.96	10	0.12	148	<1	0.31	17	730	34	20	<20	68	0.10	<10	78	<10	8	38
10	X45042	85	0.4	7.86	10	255	10	0.54	4	25	159	1076	7.33	2.00	20	1.54	358	<1	2.83	47	1130	54	10	<20	99	0.27	<10	153	<10	31	57
17	X45049	930																													
19	X45051	>1000	0.2	7.25	10	1180	30	0.30	2	24	268	385	4.47	3.04	30	0.84	387	2	0.48	38	730	67	15	<20	41	0.29	<10	143	<10	22	63
Resplit:																															
1	X45033	30	0.2	4.36	45	1600	<5	0.04	2	8	221	480	5.98	1.54	10	0.11	136	<1	0.28	15	690	36	20	<20	60	0.09	<10	66	<10	7	32
Standard:																															
Stsd3			0.3	6.01	25	1455	<5	2.48	3	23	55	42	4.41	1.44	30	1.40	2634	6	1.10	35	1690	46	<5	<20	225	0.41	<10	130	<10	26	195
OXE74		625																													

* Based on 120g

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8056S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer