Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8042

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

10-Jul-09

No. of samples received: 35
Sample Type:Core
Project: Nucleus
Shipment #: 9NFR028
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
7	8R231462	1.28	0.037
34	8R231489	1.03	0.030

QC DATA:

Standard:

Oxi67	1.84	0.054

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

7-Jul-09
Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8042
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type:Core
Project: Nucleus
Shipment #: 9NFR028
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R231456	140	0.4	6.57	50	2215	<5	0.19	2	8	158	470	2.44	3.15	20	0.71	70	2	1.64	22	230	62	<5	<20	129	0.09	<10	44	<10	7	25
2	8R231457	180	1.0	6.44	35	3790	395	0.11	2	13	166	681	2.47	2.85	30	0.35	80	2	0.91	19	190	70	<5	<20	193	0.04	<10	29	<10	10	38
3	8R231458	25	0.6	7.44	35	1370	40	0.36	3	15	98	575	3.70	2.40	30	0.74	123	2	2.54	22	860	62	<5	<20	188	0.05	<10	47	<10	10	32
4	8R231459	325	0.8	5.45	35	1355	5	0.36	3	16	102	624	4.59	1.54	10	0.56	192	3	2.06	12	790	56	<5	<20	165	0.06	<10	38	<10	7	45
5	8R231460	340	2.2	7.02	30	1670	5	0.36	3	16	102	1355	3.55	2.56	20	0.54	133	1	2.90	22	890	68	<5	<20	196	0.06	<10	50	<10	10	55
6	8R231461	<5	<0.2	6.30	10	630	<5	0.63	2	6	138	21	1.85	4.33	30	0.24	280	2	3.52	18	370	54	<5	<20	178	0.16	<10	28	<10	15	36
7	8R231462	>1000	1.2	6.28	35	2805	40	0.13	2	7	162	403	2.46	2.99	30	0.35	88	3	1.27	17	340	70	<5	<20	141	0.06	<10	35	<10	8	43
8	8R231463	225	0.4	6.52	35	2310	5	0.16	2	8	170	333	2.16	2.84	20	0.59	83	1	1.49	18	210	54	<5	<20	106	0.09	<10	42	<10	8	27
9	8R231464	620	0.8	6.00	100	4055	10	0.32	2	9	171	314	2.14	3.07	20	0.37	93	2	1.46	23	220	62	<5	<20	148	0.06	<10	36	<10	9	25
10	8R231465	15	0.4	6.22	25	1260	10	0.37	3	18	99	372	3.38	2.91	20	0.62	369	1	2.84	23	800	60	<5	<20	268	0.04	<10	46	<10	9	49
11	8R231466 Dup	20	0.2	6.12	30	1265	10	0.37	3	18	95	362	3.37	2.97	20	0.63	354	2	2.81	24	810	60	<5	<20	264	0.04	<10	45	<10	9	48
12	8R231467	150	1.0	6.32	35	825	<5	0.79	2	12	142	623	2.66	3.01	10	0.89	135	1	3.46	22	360	58	<5	<20	190	0.10	<10	60	<10	10	29
13	8R231468	125	0.8	6.68	110	785	<5	0.64	3	17	144	480	4.12	2.68	20	1.10	257	<1	3.34	26	310	62	<5	<20	157	0.12	<10	76	<10	17	60
14	8R231469	35	0.2	7.33	10	785	<5	1.76	3	18	166	116	4.23	2.55	20	1.30	320	<1	3.61	24	340	62	<5	<20	179	0.19	<10	117	<10	20	36
15	8R231470	25	0.6	8.56	15	295	<5	1.86	3	19	110	196	4.08	2.07	<10	1.46	338	<1	4.92	25	390	66	<5	<20	228	0.17	<10	97	<10	12	30
16	8R231471	15	0.6	7.85	<5	535	<5	2.08	2	13	132	164	2.83	2.04	<10	0.91	234	<1	4.49	22	280	66	<5	<20	269	0.13	<10	63	<10	10	21
17	8R231472	55	0.4	6.31	15	640	<5	1.20	3	16	122	252	5.75	1.62	10	1.39	273	6	2.71	12	270	62	<5	<20	160	0.21	<10	108	<10	11	34
18	8R231473	210	0.8	8.58	<5	175	<5	3.69	3	26	71	533	5.56	2.06	<10	2.35	624	<1	4.11	27	320	80	<5	<20	240	0.24	<10	200	<10	12	47
19	8R231474	60	0.6	8.12	10	270	<5	4.95	4	29	91	286	6.29	2.11	<10	2.51	862	<1	2.68	34	500	80	<5	<20	228	0.32	<10	224	<10	22	56
20	8R231475	325	0.8	7.88	20	330	10	2.33	3	21	112	742	5.17	2.52	<10	2.02	247	<1	2.97	29	400	72	<5	<20	170	0.24	<10	149	<10	23	36
21	8R231476	170	0.8	7.68	5	495	<5	1.98	3	20	153	574	4.91	2.44	<10	1.18	115	<1	3.06	26	360	66	<5	<20	196	0.18	<10	131	<10	12	18
22	8R231477	435	0.8	7.55	10	525	15	0.99	3	20	129	624	5.08	2.23	10	1.26	125	<1	2.62	23	460	64	<5	<20	181	0.16	<10	113	<10	12	20
23	8R231478	910	4.8	0.43	<5	<5	20	0.04	15	203	62	7890	>10	0.29	<10	0.14	<1	<1	0.46	31	40	66	10	<20	2	<0.01	<10	6	40	<1	28
24	8R231479 Dup	980	4.6	0.42	<5	<5	20	0.04	15	208	56	7858	>10	0.29	<10	0.15	<1	<1	0.43	32	40	62	10	<20	2	<0.01	<10	6	40	<1	29
25	8R231480	5	0.2	6.76	10	930	<5	1.00	2	7	144	34	1.64	1.68	30	0.36	391	2	3.44	20	430	72	<5	<20	231	0.15	<10	31	<10	16	43

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R231481	125	1.0	5.46	60	260	15	0.44	5	21	173	935	6.04	2.04	10	1.01	200	2	1.87	22	520	66	<5	<20	132	0.11	<10	96	<10	9	205
27	8R231482	255	0.4	5.31	45	615	<5	0.65	2	14	204	336	4.12	2.31	10	0.52	239	<1	1.91	22	410	54	5	<20	240	0.09	<10	66	<10	9	23
28	8R231483	570	1.6	6.86	20	395	15	0.58	3	14	133	1744	5.59	2.08	<10	1.35	210	<1	2.77	20	530	66	<5	<20	131	0.14	<10	76	<10	10	50
29	8R231484	300	0.4	6.66	10	195	<5	0.88	3	21	106	528	6.32	2.63	<10	1.87	181	<1	3.54	21	500	62	<5	<20	144	0.20	<10	134	<10	9	24
30	8R231485	285	<0.2	6.29	15	245	<5	0.56	3	13	126	388	4.58	2.29	<10	1.67	144	<1	3.50	22	340	66	<5	<20	138	0.15	<10	98	<10	6	26
31	8R231486	175	2.4	1.53	200	35	10	0.20	5	73	261	3795	>10	1.21	<10	1.33	150	<1	0.32	13	530	42	10	<20	8	0.03	<10	57	10	2	42
32	8R231487	100	0.4	7.34	20	885	<5	2.07	3	22	146	481	5.19	2.35	10	1.82	301	<1	2.76	28	390	72	<5	<20	199	0.18	<10	152	<10	11	23
33	8R231488	70	<0.2	7.45	<5	300	<5	3.29	3	22	146	190	4.84	2.05	<10	2.23	568	<1	2.86	33	470	74	<5	<20	242	0.21	<10	167	<10	16	33
34	8R231489	>1000	3.8	7.52	35	1605	5	0.97	5	17	107	3297	3.99	4.24	30	0.80	322	278	1.16	27	710	174	35	<20	163	0.29	<10	92	<10	11	183
35	8R231490	15	<0.2	7.52	15	340	30	2.89	3	24	137	235	5.03	2.27	<10	2.05	414	<1	3.08	30	410	72	<5	<20	226	0.21	<10	165	<10	16	35
QC DATA:																															
Repeat:																															
1	8R231456	150	0.4	6.47	50	2175	<5	0.19	2	8	163	478	2.41	3.07	20	0.69	70	2	1.67	20	230	58	<5	<20	124	0.09	<10	43	<10	8	25
4	8R231459	265																													
9	8R231464	575																													
10	8R231465	15	0.3	6.33	25	1235	10	0.34	3	18	98	388	3.29	2.79	10	0.64	361	1	2.90	24	840	62	<5	<20	258	0.04	<10	46	<10	9	45
19	8R231474	60	0.4	7.89	10	265	<5	4.80	4	29	92	279	6.15	2.04	<10	2.41	843	<1	2.63	35	480	80	<5	<20	223	0.31	<10	220	<10	21	56
28	8R231483	540																													
Resplit:																															
1	8R231456	120	0.4	6.69	35	2195	<5	0.18	2	7	152	470	2.13	2.99	20	0.69	64	2	1.79	19	220	60	<5	<20	129	0.09	<10	41	<10	7	23
Standard:																															
Stsd3			0.4	5.95	25	1480	<5	2.50	3	18	76	44	4.27	1.54	40	1.40	2526	5	1.25	33	1680	54	<5	<20	227	0.39	<10	128	<10	33	197
OXE74		605																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8038S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer