Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8052

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

17-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR033
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
4	8R232629	21.9	0.639

QC DATA:

Standard:

SK43	4.10	0.120

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

17-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8052
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR033
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R232626	5	0.2	8.08	25	705	<5	1.30	2	26	142	201	5.23	3.13	<10	2.40	176	2	2.14	30	470	64	<5	<20	125	0.23	<10	227	<10	5	24
2	8R232627	460	0.4	7.70	50	380	<5	2.50	2	30	155	183	6.37	2.83	<10	3.07	219	<1	2.02	33	484	66	<5	<20	189	0.27	<10	191	<10	8	31
3	8R232628	110	0.4	7.38	255	500	<5	1.83	3	23	140	418	5.48	2.79	<10	1.80	256	2	2.41	24	410	88	10	<20	145	0.24	<10	191	<10	9	104
4	8R232629	>1000	4.4	2.61	1145	215	5	2.39	3	24	80	126	4.44	0.99	<10	0.80	605	38	0.92	51	264	1268	<5	<20	71	0.04	<10	77	<10	5	296
5	8R232630	20	0.2	7.64	20	640	<5	1.86	3	27	151	277	6.14	2.95	<10	1.85	254	<1	2.92	25	494	64	<5	<20	214	0.27	<10	200	<10	12	38
6	8R232631	15	0.2	7.99	85	1075	<5	0.77	2	24	184	358	5.60	4.63	<10	1.38	171	8	2.57	28	506	64	<5	<20	153	0.16	<10	212	<10	7	29
7	8R232632	50	0.2	1.53	35	280	<5	0.25	1	17	323	427	3.12	0.78	<10	0.18	131	15	0.14	16	154	34	5	<20	23	0.06	<10	36	<10	3	50
8	8R232633	40	0.4	1.42	40	205	<5	0.36	<1	7	324	243	1.90	0.85	<10	0.39	219	11	0.30	9	176	26	5	<20	45	0.06	<10	26	<10	3	43
9	8R232634	15	0.2	0.41	50	35	<5	0.21	1	7	411	315	1.61	0.23	<10	0.15	163	14	0.02	11	66	28	5	<20	15	0.05	<10	11	<10	2	137
10	8R232635	15	0.6	5.08	35	715	5	0.95	2	23	268	632	5.77	3.28	<10	1.03	189	7	1.13	29	462	44	5	<20	93	0.09	<10	110	<10	5	25
11	8R232636	5	0.2	3.46	30	465	<5	0.30	1	16	231	313	3.29	2.79	<10	0.28	132	35	0.50	16	340	28	5	<20	60	0.07	<10	57	<10	5	16
12	8R232637	<5	0.4	6.81	135	2050	<5	1.23	2	11	119	329	2.68	4.78	30	0.65	165	4	1.99	16	682	62	<5	<20	220	0.08	<10	35	<10	9	36
13	8R232638	10	0.8	6.42	50	2200	5	0.60	2	12	138	533	5.48	5.14	30	0.55	199	6	0.92	15	638	58	<5	<20	161	0.06	<10	34	<10	6	44
14	8R232639	10	0.6	6.24	45	1855	10	0.26	2	10	112	456	5.83	4.35	30	0.42	129	2	0.87	14	628	52	<5	<20	126	0.07	<10	39	<10	7	26
15	8R232640	40	1.2	6.02	5	400	<5	0.35	3	40	146	996	>10	2.89	10	2.03	191	10	1.23	26	572	54	<5	<20	86	0.21	<10	157	<10	6	39
16	8R232641	45	5.0	0.93	<5	10	10	0.10	6	160	259	4513	>10	0.19	<10	0.59	144	<1	0.21	13	902	32	10	<20	24	0.03	<10	35	20	2	44
17	8R232642	315	5.6	0.68	<5	<5	20	0.12	12	256	82	5636	>10	0.35	<10	0.61	43	<1	0.46	19	340	56	10	<20	5	0.02	<10	20	30	<1	36
18	8R232643 Dup	365	5.6	0.66	<5	<5	25	0.11	13	269	77	5770	>10	0.35	<10	0.60	39	<1	0.47	19	330	58	10	<20	5	0.02	<10	20	30	<1	33
19	8R232644	<5	<0.2	6.73	10	1110	<5	1.19	1	9	191	25	2.17	3.45	40	0.34	428	3	4.24	18	484	64	<5	<20	316	0.21	<10	36	<10	16	44
20	8R232645	210	1.6	7.60	165	360	<5	0.31	6	53	99	915	>10	2.79	20	1.02	171	<1	2.98	19	802	276	<5	<20	79	0.12	<10	95	<10	7	317
21	8R232646	170	5.2	0.69	<5	<5	20	0.08	12	284	115	6059	>10	0.16	<10	0.37	75	<1	0.32	14	188	52	10	<20	6	0.01	<10	11	30	1	26
22	8R232647	660	4.4	2.16	<5	20	15	0.06	7	161	164	3660	>10	0.43	20	1.65	149	<1	0.41	14	132	42	10	<20	29	0.01	<10	21	20	2	61
23	8R232648	300	6.8	0.36	<5	<5	30	0.08	15	300	33	7222	>10	0.17	<10	0.19	28	<1	0.56	18	186	68	15	<20	3	0.01	<10	18	40	<1	32
24	8R232649	285	5.0	0.48	<5	<5	30	0.17	13	257	68	5350	>10	0.15	<10	0.54	135	<1	0.40	14	210	54	10	<20	8	0.01	<10	22	30	1	39
25	8R232650 Dup	230	5.4	0.41	<5	<5	25	0.13	13	256	69	5675	>10	0.14	<10	0.43	107	<1	0.38	13	176	52	10	<20	5	0.01	<10	20	30	1	35

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R232651	<5	0.2	6.18	10	980	<5	0.93	1	8	162	27	2.03	3.42	30	0.30	393	2	4.11	17	450	58	<5	<20	274	0.21	<10	32	<10	14	39
27	8R232652	35	1.2	6.84	15	65	5	0.33	5	59	118	1433	>10	3.98	10	1.46	265	<1	1.27	26	704	88	<5	<20	93	0.15	<10	107	<10	5	49
28	8R232653	250	5.8	1.35	20	15	25	0.13	9	192	219	9110	>10	0.47	<10	0.41	102	<1	0.22	29	506	50	10	<20	73	0.04	<10	42	20	1	50
29	8R232654	190	3.2	3.92	20	140	<5	0.16	3	23	261	2745	7.52	2.53	20	0.27	183	6	1.41	16	253	50	5	<20	103	0.05	<10	57	<10	5	58
30	8R232655	60	2.2	5.61	25	310	25	0.43	4	21	159	2283	9.05	2.79	50	0.59	297	<1	2.53	18	450	76	15	<20	130	0.12	<10	55	<10	10	108
31	8R232656	160	1.0	5.96	105	1255	15	0.63	2	14	160	495	4.37	2.44	20	0.46	188	6	3.83	15	484	62	5	<20	150	0.11	<10	40	<10	10	51
32	8R232657	15	0.6	6.90	20	3180	<5	0.79	2	10	172	267	2.75	3.02	190	0.34	123	34	4.92	16	506	58	<5	<20	209	0.09	<10	26	<10	14	10
33	8R232658	20	0.4	7.18	40	190	<5	1.02	4	13	135	184	4.68	1.74	20	1.62	409	1	5.21	17	1200	66	<5	<20	145	0.27	<10	62	<10	12	178
34	8R232659	165	0.2	5.20	25	1480	<5	0.62	1	8	171	278	1.64	2.12	40	0.29	153	14	4.53	15	198	50	5	<20	131	0.06	<10	23	<10	7	49
35	8R232660	15	0.4	8.06	70	190	<5	1.00	3	21	279	267	8.29	3.35	10	3.35	340	1	2.76	54	870	66	10	<20	98	0.39	<10	156	<10	9	42
QC DATA:																															
Repeat:																															
1	8R232626	10	0.2	7.90	20	675	<5	1.25	2	24	137	191	5.22	3.10	<10	2.42	165	2	2.15	27	462	60	<5	<20	119	0.21	<10	216	<10	5	22
2	8R232627	415																													
10	8R232635	30	0.8	4.95	35	690	5	0.93	2	22	255	629	5.63	3.23	<10	1.01	184	7	1.10	28	450	42	5	<20	91	0.09	<10	107	<10	5	24
20	8R232645	220	1.8	7.81	165	380	<5	0.32	6	57	105	935	>10	2.83	20	1.07	178	<1	3.02	20	824	290	<5	<20	84	0.14	<10	100	<10	8	323
23	8R232648	255																													
Resplit:																															
1	8R232626	<5	<0.2	7.71	15	645	<5	1.22	2	22	159	172	5.03	3.10	<10	2.33	165	2	2.15	28	450	60	<5	<20	119	0.22	<10	206	<10	5	20
Standard:																															
Stsd3			0.3	5.83	20	1410	<5	2.41	3	24	55	38	4.33	1.26	30	1.20	2677	7	1.12	38	1730	46	<5	<20	222	0.41	<10	129	<10	27	202
OXE74		610																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8048S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer