Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8077

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

23-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR064
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
17	X47058	1.03	0.030

QC DATA:

Standard:

Oxi67	1.82	0.053

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

22-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8077
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR064
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X47042	20	0.6	8.39	15	180	<5	3.13	6	58	175	1059	6.88	1.35	10	3.17	874	<1	2.87	70	930	110	<5	<20	138	0.71	<10	217	<10	36	97
2	X47043	15	0.2	8.55	15	230	<5	1.15	7	118	92	792	8.56	0.94	50	1.12	1382	<1	1.40	92	820	44	15	<20	70	0.76	<10	321	<10	89	122
3	X47044	35	<0.2	7.20	10	1015	<5	0.14	3	16	205	464	3.74	1.75	20	0.15	120	<1	0.55	29	360	62	30	<20	64	0.30	<10	70	<10	19	22
4	X47045	<5	<0.2	6.44	15	555	<5	0.49	1	6	123	24	1.85	4.51	40	0.19	243	4	3.84	15	270	66	<5	<20	141	0.21	<10	21	<10	17	37
5	X47046	35	<0.2	6.72	5	1165	<5	0.39	2	6	207	229	2.65	2.00	30	0.57	45	2	1.42	19	300	62	<5	<20	120	0.30	<10	42	<10	11	11
6	X47047	105	1.8	7.68	10	1105	<5	0.83	4	25	305	1017	5.03	2.68	10	1.34	199	3	1.86	48	590	40	15	<20	221	0.28	<10	121	<10	13	57
7	X47048	50	<0.2	6.98	<5	770	<5	1.14	3	20	261	739	5.00	1.56	10	1.35	132	3	3.72	30	480	78	<5	<20	153	0.36	<10	101	<10	12	30
8	X47049	20	<0.2	5.90	10	1695	<5	0.21	1	5	219	105	1.27	3.05	40	0.09	65	5	3.45	16	90	70	5	<20	96	0.01	<10	<1	<10	4	7
9	X47050 Dup	10	<0.2	5.73	10	1635	<5	0.20	1	5	220	94	1.18	2.87	40	0.09	58	5	3.34	16	80	66	5	<20	92	<0.01	<10	<1	<10	4	7
10	X47051	15	0.4	8.22	5	710	<5	1.50	4	20	184	465	4.67	2.09	20	1.36	281	<1	2.57	29	420	42	<5	<20	185	0.25	<10	119	<10	15	40
11	X47052	20	<0.2	8.04	10	880	<5	2.14	6	25	208	738	4.92	2.30	20	1.60	273	<1	2.74	34	510	44	<5	<20	206	0.27	<10	136	<10	16	43
12	X47053	25	0.4	7.86	10	1205	<5	1.38	6	21	260	623	4.82	2.70	20	1.68	189	<1	2.70	32	500	42	<5	<20	168	0.25	<10	132	<10	14	31
13	X47054	25	0.6	8.22	20	725	<5	1.42	5	46	146	457	5.98	2.42	20	1.82	783	<1	2.33	45	750	44	<5	<20	141	0.31	<10	161	<10	37	73
14	X47055	15	0.6	8.96	10	500	<5	1.16	3	14	121	238	2.68	1.51	20	0.94	294	<1	6.23	30	440	44	<5	<20	181	0.16	<10	65	<10	9	18
15	X47056	40	0.4	7.24	10	1395	<5	0.48	3	19	262	267	3.50	3.36	20	1.40	477	3	1.82	33	430	46	5	<20	105	0.23	<10	92	<10	14	38
16	X47057	140	0.6	8.32	10	1190	<5	0.94	3	14	114	256	2.54	3.21	20	1.03	280	<1	3.62	27	390	42	<5	<20	146	0.17	<10	70	<10	10	28
17	X47058	>1000	3.8	7.24	30	1470	5	0.94	6	17	109	3208	4.17	3.99	30	0.83	326	275	1.03	28	730	154	30	<20	163	0.31	<10	84	<10	9	177
18	X47059	60	0.6	8.25	10	1460	<5	0.70	3	18	223	232	3.71	3.09	20	1.19	312	2	1.61	28	430	50	<5	<20	85	0.21	<10	95	<10	10	47
19	X47060	130	0.6	8.08	55	875	<5	2.03	6	21	224	198	4.29	2.11	20	1.15	399	2	2.20	31	550	142	<5	<20	136	0.25	<10	106	<10	15	195
20	X47061	75	1.0	8.41	20	560	<5	2.43	7	35	240	738	5.24	1.52	20	1.40	849	<1	2.82	44	770	50	5	<20	290	0.29	<10	107	<10	31	156
21	X47062	65	1.2	7.00	10	1665	<5	0.30	3	8	163	1582	1.74	3.47	30	0.37	93	4	2.64	22	210	46	<5	<20	117	0.08	<10	30	<10	13	32
22	X47063	30	0.8	7.62	15	830	<5	0.44	3	19	223	3056	2.96	2.66	30	0.65	362	1	2.44	35	490	50	5	<20	99	0.21	<10	74	<10	25	54
23	X47064	45	<0.2	7.44	10	1005	<5	0.29	3	13	117	683	1.63	2.06	10	0.91	61	2	3.74	23	350	92	<5	<20	108	0.11	<10	21	<10	5	31
24	X47066	35	<0.2	7.35	10	1035	<5	1.09	3	14	183	194	3.26	3.30	40	1.46	166	<1	3.43	33	560	48	<5	<20	224	0.22	<10	69	<10	13	22
25	X47067	35	0.2	7.45	10	1160	<5	0.99	3	12	155	181	3.10	3.49	40	0.92	150	<1	2.90	24	500	42	<5	<20	237	0.20	<10	51	<10	15	14

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X47068	55	0.6	7.38	20	890	<5	1.29	3	18	176	459	4.18	3.33	50	1.49	215	<1	3.04	33	660	44	<5	<20	258	0.26	<10	80	<10	16	27
27	X47069	75	1.0	7.05	70	725	<5	1.47	3	21	146	684	4.10	3.16	30	0.83	279	<1	1.23	33	520	38	15	<20	138	0.19	<10	65	<10	15	16
28	X47070	10	0.6	7.85	5	905	<5	1.11	2	12	149	209	2.54	3.07	30	0.71	138	<1	3.37	25	440	48	<5	<20	220	0.15	<10	40	<10	11	19
29	X47071	25	0.8	7.31	10	985	<5	1.12	3	18	144	378	3.87	3.14	40	1.20	135	<1	3.19	30	620	44	<5	<20	238	0.23	<10	64	<10	14	19
30	X47072	25	0.6	7.27	10	1655	<5	0.88	3	8	164	182	2.01	3.63	40	0.65	156	1	3.20	21	320	50	<5	<20	159	0.09	<10	30	<10	8	52
31	X47073	50	0.6	7.80	15	835	<5	0.76	3	12	184	218	2.92	2.32	20	0.86	236	3	3.92	23	390	42	10	<20	132	0.15	<10	62	<10	8	39
32	X47074	80	1.0	6.52	30	505	<5	2.14	3	18	179	278	4.28	1.79	20	1.27	454	12	0.82	38	520	38	20	<20	107	0.20	<10	98	<10	11	41
33	X47075	40	0.4	7.41	85	1765	<5	1.30	2	5	123	119	1.24	3.61	<10	0.51	158	1	1.11	20	180	46	20	<20	265	0.03	<10	14	<10	5	25
34	X47076	75	0.6	7.86	10	1015	<5	1.43	3	14	138	252	3.05	2.74	20	0.82	281	<1	0.61	21	470	38	10	<20	84	0.19	<10	85	<10	12	17
QC DATA:																															
Repeat:																															
1	X47042	20	0.4	8.43	10	175	<5	2.96	5	63	177	1110	7.17	1.26	<10	3.22	886	3	2.71	69	940	112	<5	<20	148	0.68	<10	226	<10	41	90
10	X47051	20	0.2	8.48	5	710	<5	1.52	4	21	190	472	4.86	2.10	20	1.32	291	<1	2.61	30	410	42	<5	<20	192	0.25	<10	122	<10	16	40
19	X47060	155	0.6	7.03	55	840	<5	1.90	6	20	220	193	4.06	2.04	20	1.15	387	1	2.12	32	530	136	<5	<20	129	0.24	<10	99	<10	14	187
28	X47070		0.6	7.73	10	915	<5	1.16	3	13	155	218	2.70	3.26	30	0.74	147	1	3.55	23	470	50	<5	<20	239	0.15	<10	40	<10	12	21
Resplit:																															
1	X47042	15	0.6	8.66	15	190	<5	3.32	6	63	197	1091	6.82	1.45	10	2.94	917	<1	2.63	74	920	94	5	<20	158	0.64	<10	225	<10	41	105
Standard:																															
Stsd3			0.4	5.94	25	1420	<5	2.48	4	21	78	40	4.13	1.49	30	1.20	2695	7	1.24	42	1740	60	<5	<20	246	0.43	<10	126	<10	34	202
OXE74		625																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/1_td8077rS
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer