Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8082

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

24-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR060
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
10	X46046	*	3.32	0.097
20	X46056	*	1.02	0.030
31	X46067		21.5	0.627

QC DATA:

Repeat:

10	X46046	6.67	0.195
10	X46046	2.79	0.081
10	X46046	4.15	0.121
20	X46056	3.74	0.109
20	X46056	1.15	0.034
20	X46056	0.56	0.016

Standard:

SK43	4.10	0.120

* Metallic Assay Recommended

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

23-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8082
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR060
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X46036	45	0.2	6.19	20	940	<5	0.25	3	10	137	168	2.63	2.48	10	0.54	207	1	2.21	20	290	56	10	<20	102	0.07	<10	29	<10	7	84
2	X46037	<5	<0.2	6.18	50	1170	<5	0.32	2	15	197	230	3.25	2.91	20	0.87	240	1	1.88	54	360	32	15	<20	93	0.11	<10	49	<10	8	26
3	X46038	5	<0.2	6.71	30	1430	5	0.31	2	10	102	175	2.40	2.58	20	0.61	155	45	2.39	20	320	30	10	<20	119	0.11	<10	31	<10	10	16
4	X46039	45	0.4	6.40	25	1550	<5	0.25	2	10	112	292	1.92	2.96	10	0.52	99	1	1.85	18	270	30	10	<20	91	0.09	<10	23	<10	10	17
5	X46040	<5	0.2	6.39	5	1295	<5	0.13	1	2	100	29	0.50	3.58	30	0.30	36	3	0.56	14	170	30	10	<20	53	0.04	<10	15	<10	7	13
6	X46041	<5	0.4	5.56	5	1600	<5	0.08	1	2	126	88	0.57	2.91	20	0.30	74	2	0.32	12	100	42	20	<20	56	0.04	<10	10	<10	6	40
7	X46042	<5	0.6	7.18	50	1190	45	0.30	3	14	105	306	3.31	3.09	20	0.87	428	2	1.28	21	360	92	20	<20	93	0.13	<10	16	<10	14	139
8	X46043	5	0.6	7.07	55	1360	70	0.41	4	16	96	325	3.62	3.27	20	1.31	367	5	1.34	23	720	116	20	<20	97	0.20	<10	45	<10	14	165
9	X46045	<5	0.2	7.08	60	2415	5	0.30	2	10	119	159	2.46	2.61	20	0.89	192	6	2.19	18	410	48	10	<20	119	0.17	<10	24	<10	13	38
10	X46046	>1000	1.2	7.10	45	1525	245	0.99	5	11	136	413	3.13	2.56	20	1.09	343	6	2.10	23	460	138	20	<20	152	0.15	<10	30	<10	15	253
11	X46047	10	0.4	7.04	55	1200	40	0.37	2	9	127	530	2.56	2.41	10	0.87	179	2	1.70	30	360	40	15	<20	109	0.11	<10	25	<10	10	42
12	X46048	45	1.2	8.16	50	3295	35	1.06	2	9	139	1169	2.73	3.89	50	0.99	171	1	1.45	29	270	40	20	<20	151	0.08	<10	22	<10	14	32
13	X46049	<5	0.4	7.43	105	1455	<5	1.41	2	11	132	161	3.05	2.68	30	0.97	174	5	1.35	25	420	32	15	<20	119	0.18	<10	23	<10	16	13
14	X46050	<5	0.2	7.29	30	3780	<5	1.43	2	5	89	181	1.67	3.40	60	0.92	129	3	2.01	18	210	32	10	<20	161	0.07	<10	13	<10	11	7
15	X46051	<5	<0.2	6.50	60	1210	<5	1.43	2	8	101	209	2.46	2.33	20	1.06	175	3	2.13	19	340	32	10	<20	130	0.11	<10	14	<10	12	24
16	X46052	<5	<0.2	6.66	90	1410	<5	0.89	2	12	113	224	2.85	2.25	20	0.95	125	9	1.85	22	360	28	20	<20	117	0.17	<10	18	<10	14	7
17	X46053	50	0.6	7.20	60	1495	<5	0.95	4	12	106	579	3.97	3.32	20	1.30	258	4	1.53	20	500	46	15	<20	115	0.19	<10	50	<10	11	158
18	X46054	85	1.2	7.29	30	1125	<5	0.97	3	9	147	937	3.21	2.41	30	1.13	160	7	1.13	20	390	32	25	<20	99	0.13	<10	21	<10	11	20
19	X46055	10	0.6	8.56	60	3045	<5	2.39	3	11	68	553	4.11	3.67	30	1.22	411	2	0.59	21	590	46	30	<20	111	0.17	<10	46	<10	16	41
20	X46056	>1000	0.4	7.23	65	1855	<5	0.68	3	13	131	330	2.77	3.16	30	0.65	219	8	0.46	22	580	42	30	<20	73	0.16	<10	34	<10	11	18
21	X46057	<5	0.2	7.30	10	2590	<5	1.18	2	5	94	155	1.97	3.69	40	0.56	213	3	0.48	18	200	36	20	<20	102	0.05	<10	25	<10	8	13
22	X46058	70	0.6	7.07	30	865	5	1.98	4	24	112	813	5.09	3.74	30	1.35	461	<1	0.51	35	610	44	30	<20	84	0.29	<10	159	<10	9	41
23	X46059	15	0.4	6.66	70	1395	<5	2.03	4	16	101	484	4.33	4.17	20	0.93	492	<1	0.50	33	380	42	35	<20	105	0.20	<10	111	<10	10	88
24	X46060	75	0.2	5.58	25	765	5	1.39	2	7	92	200	2.13	2.59	30	0.60	338	2	0.36	17	190	30	35	<20	51	0.07	<10	35	<10	8	24
25	X46061	390	<0.2	5.02	20	530	<5	1.10	2	4	89	53	1.29	2.10	10	0.44	239	<1	0.30	13	110	32	45	<20	38	0.04	<10	27	<10	7	65

ECO TECH LABORATORY LTD. ICP CERTIFICATE OF ANALYSIS AW 2009-8082 Bushmaster Exploration

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X46062	20	1.0	7.05	35	1020	20	1.67	5	26	108	1020	5.30	3.98	20	1.42	438	2	0.53	38	670	60	30	<20	85	0.30	<10	159	<10	9	55
27	X46063	60	0.4	6.85	150	55	5	0.68	5	31	73	594	7.89	1.77	20	0.92	281	<1	0.46	33	1070	38	105	<20	41	0.28	<10	108	<10	17	16
28	X46064	165	0.4	7.74	95	240	20	0.61	6	37	59	910	7.79	2.75	20	1.16	275	1	0.54	37	1100	58	45	<20	53	0.23	<10	140	<10	13	31
29	X46065	555	0.6	7.67	15	295	70	0.66	4	27	75	679	6.04	2.62	20	0.96	114	<1	3.31	27	1130	38	<5	<20	160	0.22	<10	111	<10	14	12
30	X46066	400	0.4	7.50	70	610	40	0.69	4	22	94	456	6.16	2.96	<10	1.61	172	<1	3.23	28	1040	38	<5	<20	156	0.25	<10	168	<10	7	15
31	X46067	>1000	3.9	2.96	1090	220	10	2.29	4	22	86	130	4.19	0.99	<10	0.76	621	35	0.91	52	270	1250	5	<20	80	0.04	<10	81	<10	5	291
32	X46068	45	0.8	7.34	55	245	30	0.58	6	44	74	1436	8.88	3.23	<10	1.73	193	<1	3.04	40	1070	58	5	<20	159	0.24	<10	207	<10	7	32
33	X46069	20	1.2	7.25	30	575	5	0.63	3	20	116	1276	4.75	3.03	10	0.72	180	<1	3.09	25	810	38	<5	<20	146	0.13	<10	94	<10	11	35
34	X46070	<5	<0.2	7.02	15	785	<5	0.66	2	7	144	29	1.69	4.12	40	0.27	301	4	2.75	18	340	46	<5	<20	219	0.20	<10	29	<10	16	31
QC DATA:																															
Repeat:																															
1	X46036	60	<0.2	6.37	25	960	<5	0.26	3	10	128	169	2.53	2.48	10	0.53	200	<1	2.19	18	290	52	10	<20	101	0.07	<10	28	<10	8	86
10	X46046	>1000	1.0	6.93	45	1525	270	0.96	5	11	137	426	3.19	2.60	20	1.15	351	6	2.12	23	480	136	20	<20	151	0.16	<10	30	<10	15	246
19	X46055	5	0.8	8.02	35	2920	<5	2.23	3	11	60	528	3.54	3.43	30	1.22	361	2	0.54	21	590	48	30	<20	101	0.16	<10	40	<10	14	37
25	X46061	420																													
29	X46065	565																													
30	X46066	390																													
Resplit:																															
1	X46036	35	<0.2	6.76	20	1040	5	0.29	3	10	139	159	2.55	2.52	20	0.53	207	<1	2.26	19	290	64	10	<20	106	0.08	<10	28	<10	8	95
Standard:																															
Stsd3			0.4	5.90	30	1415	<5	2.56	4	25	71	48	4.10	1.45	30	1.43	2677	7	1.31	33	1750	60	<5	<20	242	0.39	<10	126	<10	38	195
OXE74		615																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/1_TD8081s
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer