Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8073

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

23-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR055
Submitted by: Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
4	X45176	1.40	0.041
5	X45177	4.82	0.141
10	X45182	1.74	0.051

QC DATA:

Repeat:

4	X45176	1.50	0.044
10	X45182	1.87	0.055

Standard:

OXJ64	2.39	0.070

NM/hw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

21-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8073
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR055
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X45173	25	<0.2	8.11	<5	510	<5	3.68	4	32	139	252	5.45	2.19	10	3.12	630	<1	3.19	66	510	76	5	<20	179	0.56	<10	150	<10	21	39
2	X45174	35	0.8	7.73	10	845	65	3.06	4	34	120	1216	6.06	2.54	10	2.66	680	<1	2.74	52	430	96	5	<20	269	0.37	<10	145	<10	20	73
3	X45175	60	0.4	8.85	10	300	<5	2.68	5	51	120	621	8.75	2.37	<10	3.80	583	<1	3.14	68	410	90	5	<20	137	0.89	<10	268	<10	20	52
4	X45176	>1000	1.6	8.78	35	1060	15	2.48	5	36	170	398	5.69	2.77	20	2.25	381	1	2.84	56	490	460	15	<20	189	0.75	<10	203	<10	11	201
5	X45177	>1000	2.8	5.45	15	185	<5	1.10	2	13	29	43	2.95	4.96	<10	0.14	161	351	0.75	40	500	174	10	<20	664	0.06	<10	39	<10	4	313
6	X45178	30	0.4	7.36	40	1350	<5	2.95	3	28	347	334	4.95	2.54	20	2.98	510	2	2.50	113	940	74	10	<20	233	0.31	<10	162	<10	14	73
7	X45179	60	<0.2	7.77	15	1285	<5	1.84	3	24	170	302	4.67	2.66	20	1.78	311	<1	3.02	45	660	72	<5	<20	252	0.29	<10	121	<10	18	28
8	X45180	35	0.6	7.33	5	1060	<5	1.70	4	27	140	1103	5.33	3.20	30	1.60	434	1	2.86	43	720	114	5	<20	242	0.26	<10	106	<10	16	75
9	X45181	25	<0.2	9.05	25	990	<5	2.02	5	31	114	427	6.29	3.21	30	1.51	795	17	0.85	54	470	118	25	<20	273	0.22	<10	121	<10	19	136
10	X45182	>1000	6.8	5.35	100	70	440	3.17	12	33	142	4626	7.16	2.52	20	1.31	923	2	0.55	47	300	372	90	<20	111	0.12	<10	84	<10	14	769
11	X45183	<5	<0.2	7.10	15	525	<5	0.53	2	8	129	26	1.73	4.38	30	0.21	275	4	3.94	21	270	64	<5	<20	136	0.21	<10	25	<10	20	32
12	X45184	45	<0.2	8.49	90	1960	<5	2.67	3	10	96	133	2.50	3.65	60	0.88	912	3	0.77	25	270	110	45	<20	153	0.05	<10	13	<10	10	58
13	X45185	10	<0.2	8.96	55	3520	<5	1.22	2	8	103	82	1.95	3.58	70	0.52	167	2	0.85	25	280	82	25	<20	151	0.06	<10	9	<10	9	11
14	X45186	10	<0.2	8.22	70	3995	<5	0.71	2	8	93	69	1.93	3.00	70	0.43	145	3	1.75	24	250	76	20	<20	157	0.07	<10	10	<10	9	12
15	X45187	35	0.2	7.03	50	1565	30	1.49	2	5	128	86	1.73	1.80	40	0.51	136	1	1.88	22	150	62	15	<20	102	0.06	<10	11	<10	15	10
16	X45188	10	<0.2	7.21	30	1515	<5	2.28	2	5	104	174	1.44	2.44	20	0.54	148	<1	1.80	24	210	70	10	<20	309	0.06	<10	27	<10	13	20
17	X45189	20	<0.2	7.03	50	1105	<5	2.00	2	6	132	65	1.86	1.79	20	0.71	139	<1	2.44	28	200	62	15	<20	156	0.11	<10	38	<10	19	14
18	X45190	15	0.2	7.62	20	705	<5	2.31	2	7	169	23	1.31	1.29	20	0.60	147	<1	4.56	26	300	68	<5	<20	358	0.21	<10	72	<10	16	21
19	X45191	5	<0.2	7.02	5	2100	<5	2.02	1	2	142	9	0.51	2.42	<10	0.17	101	1	3.76	20	90	64	<5	<20	449	0.05	<10	11	<10	11	5
20	X45192	<5	<0.2	7.06	10	615	<5	2.38	1	7	155	15	1.18	1.07	20	0.57	132	1	4.45	24	270	58	<5	<20	364	0.19	<10	58	<10	17	10
21	X45193	10	<0.2	6.46	10	610	<5	2.97	2	7	156	25	1.85	1.12	20	0.97	223	<1	2.82	28	290	56	10	<20	238	0.16	<10	64	<10	25	13
22	X45194	5	<0.2	6.50	<5	570	<5	2.38	2	6	189	30	1.44	0.97	30	0.60	134	<1	4.19	24	180	54	<5	<20	324	0.12	<10	42	<10	29	11
23	X45195	5	<0.2	6.55	<5	565	<5	2.39	2	6	193	31	1.45	0.92	30	0.62	136	<1	4.07	23	170	52	<5	<20	314	0.12	<10	42	<10	30	8
24	X45196	35	<0.2	7.60	15	975	<5	2.12	2	10	144	116	2.56	1.40	20	0.70	161	<1	4.21	26	350	64	5	<20	305	0.12	<10	43	<10	20	13
25	X45197	25	<0.2	7.88	30	5550	<5	1.37	2	7	107	56	1.61	2.45	50	0.35	104	3	3.82	23	270	74	<5	<20	298	0.08	<10	11	<10	9	8

Stewart Group
ECO TECH LABORATORY LTD.

ICP CERTIFICATE OF ANALYSIS AW 2009-8073

Bushmaster Exploration

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X45198	20	<0.2	8.52	25	5185	<5	1.53	2	10	113	60	1.64	2.32	60	0.35	108	4	4.31	24	310	80	5	<20	390	0.10	<10	14	<10	9	11
27	X45199	185	<0.2	6.67	15	825	<5	1.44	2	12	173	94	2.56	1.56	30	0.58	144	2	3.22	23	190	60	10	<20	140	0.10	<10	25	<10	26	8
28	X45200	25	<0.2	6.40	15	1115	<5	1.16	2	7	180	105	1.90	2.00	20	0.34	124	<1	3.21	20	160	60	10	<20	234	0.05	<10	12	<10	19	9
29	X45201	25	<0.2	7.11	10	780	<5	2.24	2	10	205	138	2.74	1.33	30	0.87	235	<1	4.58	32	400	64	5	<20	293	0.13	<10	49	<10	30	18
30	X45202	20	<0.2	6.33	10	920	<5	1.56	2	10	193	145	2.58	1.79	20	0.72	136	<1	3.78	28	420	58	5	<20	178	0.09	<10	40	<10	17	9
31	X45203	45	0.2	6.49	10	665	<5	2.15	3	20	188	273	3.89	1.59	50	0.86	240	2	3.82	31	420	60	10	<20	178	0.17	<10	73	<10	28	22
32	X45205	40	1.0	8.03	35	770	<5	3.34	8	28	128	990	6.41	2.86	90	1.69	925	1	1.26	40	1290	316	45	<20	245	0.25	<10	191	<10	29	474
33	X45206	15	1.4	6.57	40	1425	90	2.64	5	7	133	79	2.55	2.36	20	0.84	500	2	0.55	24	300	406	40	<20	157	0.07	<10	51	<10	21	306
34	X45207	5	<0.2	7.04	20	510	<5	0.61	2	8	142	22	1.71	4.57	30	0.21	267	4	3.91	20	250	64	<5	<20	152	0.20	<10	25	<10	19	32
QC DATA:																															
Repeat:																															
1	X45173	35	<0.2	8.29	<5	540	<5	3.85	4	33	147	269	5.70	2.30	10	3.20	646	<1	3.22	67	520	78	<5	<20	185	0.59	<10	161	<10	22	42
10	X45182	>1000	6.4	5.54	100	75	465	3.39	12	35	147	4689	7.38	2.59	20	1.37	949	2	0.57	50	310	382	95	<20	117	0.13	<10	89	10	15	785
19	X45191	5	<0.2	6.75	<5	2030	<5	1.98	1	2	154	9	0.51	2.25	<10	0.17	100	1	3.74	21	90	64	<5	<20	434	0.05	<10	11	<10	11	5
27	X45199	190																													
28	X45200	25																													
Resplit:																															
1	X45173	25	0.2	8.08	<5	520	<5	3.87	4	33	158	276	5.70	2.25	10	3.14	645	<1	3.30	68	500	82	<5	<20	185	0.66	<10	166	<10	22	43
Standard:																															
Stsd3			0.3	5.94	25	1425	<5	2.49	4	25	73	40	4.19	1.38	30	1.32	2651	6	1.14	47	1690	64	<5	<20	235	0.42	<10	123	<10	39	213
SF30		820																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/ap
df/
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer