Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8039

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

8-Jul-09

No. of samples received: 35
Sample Type:Core
Project: Nucleus
Shipment #:9NFR023
Submitted by:Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
21	8R231406	21.5	0.627

QC DATA:

Standard:

SK43	4.05	0.118

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

7-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8039

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type:Core
Project: Nucleus
Shipment #:9NFR023
Submitted by:Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R231386	70	2.0	6.74	30	2855	95	1.37	3	12	133	1138	2.13	4.72	60	0.46	138	<1	2.71	17	520	106	<5	<20	252	0.06	<10	27	<10	11	106
2	8R231387	40	0.8	7.72	10	900	<5	1.89	3	20	109	614	3.78	2.92	20	1.05	119	<1	3.37	20	1280	62	<5	<20	489	0.20	<10	79	<10	9	17
3	8R231388	35	0.8	6.17	20	1865	<5	1.29	2	12	128	653	2.07	4.85	50	0.37	83	<1	2.64	15	280	60	<5	<20	267	0.05	<10	19	<10	8	31
4	8R231389	40	0.8	7.53	10	870	<5	1.53	3	19	104	591	3.25	3.20	20	0.96	105	<1	3.18	19	1170	62	<5	<20	405	0.18	<10	70	<10	10	19
5	8R231390	60	0.6	6.18	25	1160	<5	1.25	2	13	148	562	2.20	4.03	10	0.56	95	<1	2.16	16	590	48	10	<20	248	0.09	<10	44	<10	6	22
6	8R231391	55	1.0	7.29	25	1085	<5	1.80	3	21	90	699	3.67	3.75	20	1.13	129	<1	2.73	20	1320	58	5	<20	262	0.19	<10	77	<10	10	20
7	8R231392	45	1.2	7.61	25	1000	<5	1.54	3	22	148	824	3.91	3.29	30	1.09	130	<1	2.34	21	1370	62	10	<20	275	0.20	<10	84	<10	11	24
8	8R231393	35	1.0	7.94	40	920	<5	2.18	3	17	143	584	3.43	4.10	50	1.06	228	<1	1.21	20	1020	66	20	<20	162	0.16	<10	61	<10	11	21
9	8R231394	20	1.2	7.54	75	885	40	1.69	2	7	119	360	2.17	5.16	80	0.62	210	<1	0.71	17	210	92	35	<20	154	0.03	<10	12	<10	9	47
10	8R231395	20	0.4	6.71	30	1305	<5	1.67	2	9	145	196	1.58	3.30	<10	0.75	127	<1	3.46	24	100	58	10	<20	356	0.05	<10	20	<10	5	20
11	8R231396	35	0.4	6.37	30	1400	<5	1.28	2	7	148	150	1.21	3.19	<10	0.45	95	<1	3.52	21	150	56	10	<20	257	0.02	<10	11	<10	4	17
12	8R231397	15	0.6	6.53	25	5290	<5	2.67	2	6	131	95	2.18	4.51	60	0.74	348	<1	0.93	15	170	62	15	<20	163	0.04	<10	10	<10	9	13
13	8R231398	20	0.6	7.40	110	450	<5	1.83	2	7	103	150	3.02	4.07	80	0.61	316	<1	0.70	16	210	64	45	<20	153	0.04	<10	13	<10	9	12
14	8R231399	20	<0.2	7.02	125	160	10	2.04	3	13	95	317	4.46	4.06	140	0.84	361	<1	0.61	17	510	62	70	<20	106	0.10	<10	35	<10	15	13
15	8R231400	70	0.8	5.89	150	160	170	5.01	7	19	124	642	8.33	1.93	10	2.13	1200	<1	0.62	35	380	134	85	<20	78	0.25	<10	128	10	26	213
16	8R231401	<5	0.2	6.48	15	535	<5	0.45	1	5	123	26	1.76	4.89	30	0.18	232	3	3.31	14	250	60	<5	<20	142	0.17	<10	20	<10	15	30
17	8R231402	50	0.6	9.39	95	180	<5	1.31	4	37	290	443	5.31	1.27	20	1.22	472	<1	0.66	73	540	70	30	<20	56	0.47	<10	222	10	15	88
18	8R231403	145	0.4	8.42	10	535	<5	2.43	3	28	227	310	4.57	3.48	20	2.44	273	<1	1.47	59	370	70	5	<20	156	0.35	<10	159	<10	18	27
19	8R231404	10	0.2	6.95	5	470	<5	3.26	3	27	239	203	5.36	3.28	<10	3.98	649	<1	2.84	69	320	70	<5	<20	129	0.34	<10	163	<10	18	52
20	8R231405	5	0.2	6.71	5	555	<5	2.18	3	21	205	208	4.18	3.03	20	2.67	396	<1	3.04	49	270	62	<5	<20	130	0.27	<10	119	<10	17	37
21	8R231406	>1000	3.2	2.87	1090	215	10	2.26	3	18	79	111	4.35	1.27	<10	0.70	579	38	0.90	61	270	1218	<5	<20	78	0.03	<10	75	<10	5	275
22	8R231407	20	<0.2	7.43	40	420	<5	1.70	3	20	206	276	4.33	3.18	20	2.42	246	<1	3.20	51	450	66	<5	<20	169	0.28	<10	109	<10	16	26
23	8R231408	60	0.4	5.91	35	390	<5	1.30	3	22	135	463	4.28	2.52	20	1.67	200	<1	2.54	33	460	60	<5	<20	154	0.32	<10	132	<10	20	27
24	8R231409	20	0.4	6.53	25	785	<5	1.54	3	18	179	287	3.79	2.83	30	1.66	208	1	3.08	37	340	64	<5	<20	132	0.24	<10	96	<10	17	27
25	8R231410	25	0.3	6.11	75	5680	<5	1.29	2	6	92	131	1.42	3.71	80	0.24	92	2	3.33	15	220	64	<5	<20	264	0.06	<10	10	<10	7	15

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R231411 Dup	35	0.2	6.29	70	5635	<5	1.25	2	6	103	126	1.39	3.60	80	0.25	91	2	3.28	16	230	64	<5	<20	259	0.05	<10	10	<10	7	16
27	8R231412	20	0.2	6.30	150	5095	<5	1.37	3	7	105	333	1.72	4.28	90	0.38	118	2	2.78	16	240	102	10	<20	221	0.04	<10	9	<10	8	162
28	8R231413	15	0.2	6.10	60	645	<5	1.13	2	13	159	203	3.54	2.55	30	1.58	166	<1	2.77	17	470	54	<5	<20	125	0.22	<10	26	<10	19	26
29	8R231414	15	<0.2	5.93	40	1640	<5	1.17	2	15	151	348	3.42	3.19	20	1.10	174	1	2.65	24	360	58	<5	<20	148	0.12	<10	28	<10	18	22
30	8R231415	370	0.8	7.70	275	1410	40	0.58	2	8	108	188	3.35	4.43	20	0.64	125	1	2.19	21	440	58	15	<20	146	0.13	<10	77	<10	9	35
31	8R231416	60	0.6	7.41	160	1765	15	0.17	2	2	178	60	1.23	5.00	<10	0.11	29	1	2.45	16	50	62	5	<20	287	0.01	<10	12	<10	3	16
32	8R231417	20	0.2	7.24	300	1665	<5	0.25	2	4	132	142	2.07	4.68	<10	0.06	40	1	3.36	18	100	56	<5	<20	296	<0.01	<10	9	<10	4	32
33	8R231418 Dup	25	0.4	7.11	295	1640	<5	0.25	2	4	144	147	2.12	4.77	<10	0.06	42	1	3.35	18	110	56	<5	<20	292	<0.01	<10	9	<10	4	34
34	8R231419	70	0.2	6.95	105	1635	<5	0.25	1	2	116	55	0.81	4.53	10	0.06	29	1	3.42	14	70	56	<5	<20	229	0.01	<10	9	<10	3	13
35	8R231420	110	0.8	8.83	60	215	<5	1.29	4	15	62	573	6.05	2.89	<10	1.86	196	<1	4.44	26	720	66	<5	<20	223	0.25	<10	159	<10	8	49
QC DATA:																															
Repeat:																															
1	8R231386	50	1.8	6.61	25	2965	100	1.39	3	12	133	1169	2.14	4.82	60	0.45	138	<1	2.76	17	520	106	<5	<20	257	0.06	<10	29	<10	11	111
10	8R231395	15	0.6	6.86	35	1315	<5	1.66	2	9	145	190	1.61	3.27	<10	0.77	128	<1	3.41	24	110	58	10	<20	358	0.04	<10	20	<10	5	19
18	8R231403	95																													
19	8R231404	15	0.2	6.85	5	480	<5	3.36	3	27	234	201	5.37	3.22	<10	3.92	642	<1	2.80	70	320	70	<5	<20	135	0.32	<10	164	<10	18	55
30	8R231415	410																													
Resplit:																															
1	8R231386	60	2.2	7.03	30	2800	110	1.42	3	13	120	1195	2.26	4.37	60	0.49	142	<1	1.92	16	560	104	<5	<20	272	0.06	<10	32	<10	12	94
Standard:																															
OREAS43P			0.7	4.95	105	460	5	0.34	6	75	1015	453	>10	2.02	30	0.58	590	124	0.16	475	360	150	15	<20	40	0.28	<10	70	10	17	436
OXE74		605																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_Td8038S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer