22-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8080
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR052
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	8R232836	395	3.2	4.53	20	55	50	0.33	6	78	224	2660	>10	2.18	20	1.52	216	<1	0.99	29	710	8	10	20	86	0.21	<10	139	10	15	38
2	8R232837	330	2.6	7.98	10	870	55	0.71	4	32	141	2044	7.51	3.70	<10	1.38	162	<1	2.78	28	420	16	<5	<20	171	0.24	<10	209	<10	10	26
3	8R232838	200	0.8	7.40	10	350	50	0.88	4	28	154	882	7.56	2.52	<10	1.71	175	<1	2.95	25	470	14	<5	<20	156	0.24	<10	194	<10	10	25
4	8R232839	135	0.4	7.50	10	690	65	2.09	3	27	137	470	6.48	2.25	10	1.51	341	<1	2.88	23	670	14	<5	<20	262	0.25	<10	186	<10	12	33
5	8R232840	950	1.6	7.30	10	370	65	0.76	5	38	149	1485	8.99	2.40	10	1.52	317	<1	2.70	26	520	70	5	<20	149	0.21	<10	182	<10	12	122
6	8R232841	390	0.2	7.58	15	230	10	0.97	4	39	144	737	8.41	1.90	<10	1.58	312	<1	3.22	37	430	16	5	<20	144	0.23	<10	194	<10	11	36
7	8R232842	115	0.4	8.43	25	855	10	0.50	5	39	208	327	8.87	3.40	10	0.98	872	<1	0.70	33	610	22	20	<20	76	0.32	<10	250	<10	21	73
8	8R232843	95	0.4	7.04	140	565	5	0.36	9	43	214	439	9.11	2.23	30	0.70	1084	<1	0.49	41	440	30	45	<20	92	0.29	<10	151	<10	23	270
9	8R232844	725	8.2	6.92	35	755	<5	2.90	7	32	121	1401	5.99	1.56	10	1.71	766	54	1.92	190	800	314	15	<20	251	0.39	<10	142	<10	15	692
10	8R232845	10	0.2	6.52	15	895	<5	0.43	3	17	211	169	4.74	3.78	20	0.78	356	2	2.98	30	350	18	5	<20	103	0.19	<10	96	<10	9	34
11	8R232846	220	0.4	6.64	15	945	10	0.60	3	28	299	306	6.43	3.30	30	1.78	214	1	2.28	50	340	12	<5	<20	118	0.32	<10	140	<10	12	30
12	8R232847	130	0.4	7.24	70	700	<5	1.08	2	20	248	40	4.02	3.00	30	1.20	310	2	3.27	40	320	16	<5	<20	212	0.32	<10	100	<10	16	36
13	8R232848	55	<0.2	7.08	10	315	<5	2.30	3	26	281	105	5.50	2.20	20	2.16	377	2	2.75	47	370	12	<5	<20	169	0.38	<10	153	<10	16	34
14	8R232849	90	0.4	6.89	10	1040	<5	1.15	2	18	249	142	4.04	3.26	40	1.38	194	1	2.79	35	480	14	<5	<20	139	0.30	<10	103	<10	15	22
15	8R232850	90	<0.2	7.14	15	785	<5	1.25	3	23	224	155	4.54	2.60	40	1.10	402	2	2.84	33	480	16	<5	<20	142	0.29	<10	106	<10	19	58
16	8R232851	60	0.2	7.09	10	290	<5	2.06	3	26	251	129	5.55	2.27	20	2.19	344	<1	2.65	48	400	12	<5	<20	156	0.39	<10	152	<10	15	33
17	8R232852	50	0.2	6.68	125	1060	<5	0.74	3	21	215	238	4.39	2.83	40	1.07	268	1	2.84	39	360	16	<5	<20	132	0.21	<10	74	<10	13	61
18	8R232853	120	0.4	7.72	25	810	<5	1.40	3	30	188	313	6.62	3.59	30	1.86	368	2	2.81	50	720	20	5	<20	170	0.43	<10	178	<10	19	40
19	8R232854	135	0.4	6.98	25	795	<5	0.91	3	24	322	303	5.41	3.16	30	1.19	267	<1	1.22	48	640	12	10	<20	80	0.38	<10	139	<10	14	22
20	8R232855	195	0.6	6.26	35	1015	<5	0.63	2	27	191	403	5.45	3.25	40	0.62	402	1	1.61	42	430	12	20	<20	85	0.25	<10	105	<10	20	43
21	8R232856	265	0.6	7.07	15	925	30	0.66	3	26	211	311	7.13	3.45	30	1.65	366	1	1.94	44	550	16	10	<20	98	0.45	<10	183	<10	17	39
22	8R232857	220	0.4	7.24	10	1635	<5	0.26	2	15	215	243	4.32	4.49	40	0.49	303	2	0.84	30	260	18	15	<20	73	0.16	<10	83	<10	15	32
23	8R232858	95	0.4	6.29	10	1915	<5	0.11	2	11	214	111	2.30	4.43	40	0.12	258	2	0.50	18	90	20	20	<20	71	0.02	<10	20	<10	8	35
24	8R232859	60	0.4	5.94	25	1695	<5	0.21	2	15	178	169	2.67	4.26	40	0.20	354	2	1.09	17	170	18	20	<20	92	0.03	<10	22	<10	9	54
25	8R232860	410	1.4	5.53	65	855	65	0.13	5	19	216	615	3.71	3.14	50	0.21	437	2	0.43	20	160	172	45	<20	73	0.04	<10	20	<10	13	426

ECO TECH LABORATORY LTD. **ICP CERTIFICATE OF ANALYSIS AW 2009-8080** **Bushmaster Exploration**

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	8R232862	65	2.4	5.82	30	605	30	0.60	7	40	165	3157	7.71	4.43	40	1.19	426	2	1.66	40	1670	110	25	<20	84	0.18	<10	171	<10	15	395
27	8R232863	<5	0.2	6.74	20	505	<5	0.51	1	6	171	21	1.80	4.63	40	0.17	251	4	3.37	12	260	34	<5	<20	146	0.20	<10	27	<10	18	30
28	8R232864	760	0.8	6.78	25	520	5	0.32	2	21	162	530	4.87	4.47	140	0.37	363	3	0.74	23	750	18	25	<20	92	0.06	<10	68	<10	18	50
29	8R232865	95	1.2	8.16	20	1280	<5	0.60	3	27	103	614	6.78	4.21	20	1.10	291	<1	0.89	22	1270	18	15	<20	97	0.35	<10	234	<10	10	31
30	8R232866	50	0.4	5.40	15	2365	<5	0.55	1	11	204	253	2.52	3.73	90	0.20	76	3	2.70	16	240	14	10	<20	128	0.05	<10	20	<10	10	14
31	8R232867	205	0.6	5.44	20	1720	<5	0.75	1	9	167	254	2.30	3.69	30	0.30	80	2	2.56	14	440	12	10	<20	142	0.07	<10	34	<10	9	13
32	8R232868	150	0.8	6.51	15	380	<5	0.55	4	37	86	1039	>10	3.98	10	2.81	213	<1	1.27	29	1020	14	10	<20	71	0.53	<10	371	10	11	30
33	8R232869	235	0.8	6.73	20	1415	<5	0.65	2	12	155	462	3.06	3.29	10	0.53	117	<1	3.25	18	620	14	5	<20	304	0.09	<10	52	<10	6	21
34	8R232870	245	1.0	6.56	10	205	10	0.84	4	37	168	698	9.92	3.67	10	3.40	376	<1	1.79	35	900	14	<5	<20	158	0.47	<10	288	<10	16	38
QC DATA:																															
Repeat:																															
1	8R232836	415	3.2	4.68	20	60	45	0.35	6	82	232	2738	>10	2.31	20	1.57	222	<1	0.97	30	740	8	10	20	90	0.23	<10	146	20	16	38
3	8R232838	170																													
5	8R232840	890																													
7	8R232842	120																													
10	8R232845	10	0.4	6.82	20	950	<5	0.44	3	19	226	183	4.99	3.98	20	0.81	368	1	3.06	33	380	22	5	<20	110	0.21	<10	101	<10	10	34
11	8R232846	220																													
13	8R232848	70																													
18	8R232853	140																													
19	8R232854	125	0.6	7.24	25	840	<5	0.93	3	25	336	315	5.64	3.29	30	1.30	279	2	1.28	52	670	14	10	<20	83	0.39	<10	146	<10	14	22
25	8R232860	390																													
28	8R232864	720	0.8	6.60	20	505	<5	0.30	2	19	154	521	4.66	4.32	130	0.35	354	3	0.72	22	720	16	20	<20	86	0.06	<10	63	<10	17	50
32	8R232868	170																													
33	8R232869	240																													
Resplit:																															
1	8R232836	385	3.2	4.59	15	60	40	0.34	5	75	247	2592	>10	2.39	20	1.48	217	<1	1.03	29	680	6	10	<20	86	0.23	<10	152	10	15	39
Standard:																															
Stsd3			0.4	5.91	25	1415	<5	2.44	3	22	74	39	4.21	1.50	30	1.18	2653	7	1.15	38	1760	50	<5	<20	237	0.44	<10	131	<10	38	206
OXE74		610																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/1_TD8079s
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer