Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8069

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

23-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR043
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
3	X44038		1.60	0.047
5	X44040		1.23	0.036
10	X44045		1.12	0.033
28	X44063	*	3.22	0.094
29	X44064 Dup	*	2.48	0.072
30	X44065		1.68	0.049

QC DATA:

Repeats:

5	X44040	1.31	0.038
30	X44065	1.62	0.047

Standard:

OXI67	1.84	0.054

* Based on 120g

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

21-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8069
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type:Core
Project:Nucleus
Shipment #:9NFR043
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X44036	180	0.8	7.97	130	220	<5	0.72	5	26	249	3398	6.57	2.01	10	1.56	143	<1	2.83	41	690	44	15	<20	108	0.53	<10	191	<10	31	46
2	X44037	790	1.8	8.39	220	295	<5	0.79	5	21	266	1371	6.84	3.02	20	1.64	192	<1	2.90	52	680	40	15	<20	106	0.30	<10	167	<10	23	40
3	X44038	>1000	3.4	7.98	1270	375	75	0.45	5	16	218	1078	6.26	3.33	20	1.27	114	<1	1.81	35	590	38	25	<20	77	0.28	<10	130	<10	22	32
4	X44039	* 975	0.6	8.18	1480	490	10	0.32	4	8	170	286	4.77	2.79	20	0.73	57	<1	2.38	27	510	36	15	<20	83	0.20	<10	127	<10	10	20
5	X44040	>1000	0.6	7.89	9590	475	<5	0.24	4	10	164	652	4.68	2.73	<10	0.65	60	<1	1.97	24	620	34	20	<20	66	0.20	<10	148	<10	9	18
6	X44041	555	0.6	8.34	2385	580	<5	0.27	5	9	155	378	5.87	2.69	10	0.58	59	<1	1.43	25	670	36	40	<20	62	0.20	<10	170	<10	11	20
7	X44042	580	0.6	8.85	150	435	<5	0.30	3	11	213	518	4.13	2.08	10	1.12	111	<1	1.25	31	490	36	15	<20	45	0.29	<10	169	<10	23	21
8	X44043	190	0.4	8.87	520	585	<5	0.14	4	10	218	418	4.58	2.52	10	1.02	98	<1	0.68	35	620	36	15	<20	28	0.28	<10	183	<10	10	18
9	X44044	420	0.6	8.42	470	160	<5	0.10	5	12	230	496	7.65	2.14	20	1.02	67	<1	0.65	30	510	36	20	<20	12	0.38	<10	192	10	7	29
10	X44045	>1000	1.4	8.50	845	355	65	0.08	6	8	183	474	9.23	3.09	20	0.79	72	<1	0.66	29	720	38	30	<20	23	0.16	<10	179	10	7	36
11	X44046	110	0.2	6.12	1240	1130	15	0.05	2	2	176	436	3.51	3.63	20	0.08	27	<1	0.54	16	330	34	25	<20	37	0.01	<10	9	<10	3	3
12	X44047	275	0.6	6.12	1445	1170	15	0.05	2	1	171	329	2.22	3.69	20	0.07	28	<1	0.52	16	270	36	20	<20	38	0.01	<10	7	<10	4	<1
13	X44048	215	0.4	6.34	660	1305	10	0.05	2	1	175	64	1.81	4.15	20	0.07	29	2	0.54	16	120	38	20	<20	38	0.02	<10	7	<10	3	<1
14	X44049	220	0.6	5.98	1270	1215	15	0.05	2	1	183	83	2.91	3.86	20	0.06	27	1	0.53	17	90	36	25	<20	39	0.01	<10	7	<10	2	<1
15	X44050	175	0.6	4.85	1000	960	35	0.05	4	2	136	307	5.66	2.83	20	0.06	17	<1	0.45	15	220	32	50	<20	32	0.01	<10	13	<10	2	2
16	X44051	610	0.2	9.14	<5	105	<5	2.91	3	31	71	23	3.92	3.89	10	1.87	492	1	4.20	90	1160	58	<5	<20	356	0.59	<10	73	<10	6	44
17	X44052	505	1.0	6.89	340	800	<5	0.08	4	5	117	208	6.41	2.33	20	0.34	33	<1	0.59	20	630	32	25	<20	33	0.14	<10	61	<10	3	5
18	X44053	625	0.8	8.64	55	240	<5	0.31	4	25	194	2213	3.76	1.41	20	1.96	206	<1	0.61	70	930	40	20	<20	52	0.30	<10	120	<10	11	32
19	X44054	25	0.3	7.50	10	405	30	1.17	5	34	178	309	7.17	1.67	10	1.88	848	<1	2.21	37	1050	36	10	<20	177	0.31	<10	123	<10	29	80
20	X44055	10	0.2	7.61	10	400	<5	2.44	7	49	82	133	>10	1.37	20	2.08	1952	<1	2.10	40	1310	38	5	<20	250	0.55	<10	243	10	25	125
21	X44056	275	<0.2	8.37	15	385	<5	3.33	8	59	95	179	>10	2.15	10	4.23	3126	<1	1.92	60	1160	44	<5	<20	113	0.61	<10	317	10	20	169
22	X44057	5	<0.2	6.78	15	495	<5	0.48	2	6	120	26	1.63	4.54	30	0.21	239	4	3.49	19	250	42	<5	<20	146	0.17	<10	21	<10	14	34
23	X44058	300	0.4	6.76	40	285	<5	0.30	4	24	190	513	6.24	1.38	20	1.22	526	<1	0.76	30	380	30	25	<20	27	0.21	<10	39	<10	23	45
24	X44059	750	<0.2	7.34	25	375	<5	1.13	8	48	99	227	>10	1.70	10	2.46	1710	<1	1.57	49	980	38	10	<20	80	0.54	<10	247	10	28	117
25	X44060	480	<0.2	7.59	70	200	10	0.42	6	25	94	889	7.32	2.97	60	0.64	1061	<1	1.40	44	740	36	20	<20	81	0.09	<10	42	<10	23	34

* Based on 120g

Stewart Group
ECO TECH LABORATORY LTD.

ICP CERTIFICATE OF ANALYSIS AW 2009-8069

Bushmaster Exploration

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X44061	380	0.4	8.18	60	345	<5	0.55	5	40	135	608	6.93	1.84	40	1.11	511	<1	0.61	45	1530	34	30	<20	25	0.19	<10	104	<10	30	52
27	X44062	650	1.0	8.84	30	275	<5	0.51	5	34	175	518	5.55	1.73	20	1.45	317	<1	0.83	39	1490	38	10	<20	24	0.23	<10	104	<10	19	58
28	X44063	>1000	0.4	8.10	40	290	<5	0.60	6	44	391	484	8.21	2.61	10	2.77	606	<1	1.03	114	1390	38	15	<20	31	0.34	<10	187	<10	24	60
29	X44064 Dup	>1000	0.2	8.01	75	280	<5	0.58	6	41	375	452	7.96	2.49	10	2.77	586	<1	0.98	108	1360	36	15	<20	28	0.32	<10	177	<10	22	55
30	X44065	>1000	0.4	8.00	35	310	10	0.80	4	32	105	472	4.76	1.73	10	1.37	153	<1	3.44	52	1470	30	10	<20	99	0.21	<10	94	<10	12	18
31	X44066	845	1.0	8.75	50	300	<5	0.27	4	40	104	1379	3.83	2.48	20	0.93	75	<1	1.32	63	1230	32	30	<20	36	0.16	<10	95	<10	13	54
32	X44068	830	0.6	7.88	90	1635	15	0.08	2	9	101	855	1.92	3.79	30	0.20	24	2	0.55	33	720	30	40	<20	61	0.09	<10	32	<10	7	15
33	X44069	860	0.4	7.55	105	1675	<5	0.08	2	5	96	839	1.23	3.52	30	0.15	15	3	0.53	34	590	28	35	<20	45	0.11	<10	32	<10	6	5
34	X44070	670	0.2	7.23	210	1340	<5	0.07	2	4	125	281	1.67	3.61	30	0.15	16	3	0.54	29	470	28	40	<20	47	0.08	<10	32	<10	5	1
QC DATA:																															
Repeat:																															
1	X44036	175	0.8	8.08	130	220	<5	0.70	5	25	238	3390	6.40	1.98	10	1.59	139	<1	2.77	42	680	38	15	<20	105	0.52	<10	180	<10	30	42
10	X44045	>1000	1.6	8.70	795	340	60	0.08	6	8	174	464	8.94	2.90	20	0.77	67	<1	0.65	28	680	38	25	<20	21	0.16	<10	166	<10	7	35
17	X44052	480																													
19	X44054	15	0.4	7.58	5	415	30	1.14	5	34	171	305	6.98	1.64	10	1.90	827	<1	2.15	37	1040	36	10	<20	176	0.31	<10	121	<10	29	76
25	X44060	470																													
32	X44068	780																													
Resplit:																															
1	X44036	>1000	0.7	7.87	125	210	<5	0.65	4	24	222	3481	6.45	1.82	10	1.55	121	<1	2.54	40	640	36	15	<20	94	0.49	<10	175	<10	26	40
Standard:																															
Stsd3			0.4	6.03	25	1410	<5	2.47	4	22	72	45	4.35	1.47	30	1.41	2710	6	1.12	34	1710	62	<5	<20	240	0.41	<10	133	<10	35	210
SF30		825																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/ap
df/
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer