Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8083

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

24-Jul-09

Attn: Graeme Hopkins

No. of samples received: 34
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR063
Submitted by:Roger Hulstein

ET #.	Tag #	Au (g/t)	Au (oz/t)
5	X46075	1.43	0.042
6	X46076 Dup	2.19	0.064
17	X46087	4.87	0.142

QC DATA:

Repeat:

5	X46075	1.59	0.046
6	X46076 Dup	1.86	0.054

Standard:

SK43	4.04	0.118

NM/nw
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

23-Jul-09

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8083
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 34
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR063
Submitted by:Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X46071	50	8.4	7.45	25	1195	1790	1.20	16	28	92	3428	6.73	3.08	20	0.79	622	<1	2.74	33	1410	798	40	<20	145	0.13	<10	183	<10	9	1105
2	X46072	60	4.4	7.01	20	420	355	0.79	9	33	80	2454	7.84	2.32	10	0.70	510	<1	2.98	30	1370	478	25	<20	142	0.21	<10	158	<10	13	369
3	X46073	20	1.4	6.41	40	1220	220	0.77	3	5	175	119	2.03	2.12	20	0.42	166	<1	3.08	18	260	232	15	<20	131	0.05	<10	35	<10	6	82
4	X46074	15	<0.2	6.07	20	830	<5	0.48	3	20	147	365	4.84	2.44	40	0.79	127	<1	2.34	24	550	70	5	<20	131	0.15	<10	67	<10	12	11
5	X46075	>1000	<0.2	6.42	20	910	15	0.82	5	26	116	458	6.70	2.47	10	1.91	190	<1	1.83	38	670	90	<5	<20	129	0.23	<10	158	<10	11	21
6	X46076 Dup	>1000	0.4	6.74	20	850	20	0.84	5	26	117	456	7.19	2.51	10	1.90	204	<1	1.94	37	690	90	<5	<20	136	0.24	<10	162	<10	12	22
7	X46077	630	0.4	5.98	10	490	<5	1.13	4	22	149	341	5.25	1.58	10	1.14	195	<1	2.65	23	1440	68	<5	<20	171	0.28	<10	31	<10	25	12
8	X46078	230	0.6	5.83	10	565	<5	0.93	3	16	139	490	4.33	2.03	10	1.07	248	<1	2.25	23	1130	70	<5	<20	139	0.21	<10	22	<10	19	22
9	X46079	10	0.6	4.55	10	1435	<5	0.41	2	9	216	390	2.35	2.21	20	0.65	121	2	0.65	25	310	46	<5	<20	69	0.11	<10	75	<10	11	15
10	X46080	20	0.6	5.91	15	1535	<5	1.35	3	15	225	450	3.75	2.43	30	0.91	209	<1	0.74	25	310	66	10	<20	109	0.12	<10	63	<10	11	12
11	X46081	15	1.4	7.01	20	1585	<5	0.98	4	16	166	1500	4.46	2.90	20	0.80	157	<1	2.60	26	430	78	5	<20	199	0.13	<10	84	<10	8	29
12	X46082	60	0.2	7.38	15	1290	<5	0.69	4	24	148	650	6.06	2.84	30	0.76	188	1	2.89	24	710	74	10	<20	161	0.21	<10	84	<10	17	15
13	X46083	<5	0.2	7.16	25	1395	<5	0.72	3	6	131	211	2.25	3.04	60	0.58	198	<1	2.67	18	300	84	10	<20	144	0.07	<10	34	<10	8	50
14	X46084	10	0.4	6.86	15	1890	<5	0.95	4	12	173	540	3.69	2.96	40	0.65	264	1	2.68	21	250	140	10	<20	163	0.08	<10	61	<10	9	134
15	X46085	10	0.6	7.08	15	590	25	0.78	4	18	135	566	4.38	1.77	20	0.69	181	<1	1.10	21	360	82	15	<20	84	0.16	<10	79	<10	10	60
16	X46086	65	0.8	7.35	100	955	10	2.09	5	27	99	926	6.99	2.69	20	1.06	465	<1	0.46	37	800	98	45	<20	114	0.18	<10	151	<10	12	51
17	X46087	>1000	3.0	5.12	15	210	<5	0.99	3	11	31	54	3.08	4.66	<10	0.12	144	375	0.65	40	490	172	10	<20	579	0.06	<10	37	<10	4	307
18	X46088	15	1.0	7.39	25	885	5	2.33	4	14	151	743	4.87	2.56	40	1.09	540	<1	0.44	29	270	94	25	<20	131	0.07	<10	63	<10	12	48
19	X46089	990	6.6	3.01	110	370	70	5.85	29	29	133	5514	9.99	1.58	10	2.22	1046	<1	0.33	24	260	620	40	<20	127	0.04	<10	50	<10	13	2457
20	X46090	<5	<0.2	6.97	20	500	<5	0.52	2	6	123	40	1.90	4.39	30	0.18	270	4	3.17	16	230	70	<5	<20	153	0.21	<10	24	<10	17	29
21	X46091	5	1.6	6.45	190	145	<5	2.77	10	12	123	270	5.17	2.71	50	0.96	366	1	0.42	21	270	488	65	<20	134	0.07	<10	29	<10	11	604
22	X46092	5	0.8	6.83	25	1440	<5	2.49	4	12	145	260	3.68	1.98	30	1.07	565	2	1.58	22	350	158	10	<20	161	0.13	<10	26	<10	12	101
23	X46093	<5	0.4	6.25	20	745	<5	2.05	3	9	138	79	2.59	1.38	20	0.87	163	2	2.53	20	350	74	<5	<20	169	0.15	<10	13	<10	8	23
24	X46094	<5	0.2	6.64	20	1010	<5	1.68	4	10	141	64	2.96	2.30	20	1.12	211	2	1.64	20	280	92	<5	<20	154	0.13	<10	17	<10	9	177
25	X46096	<5	0.2	6.54	10	730	<5	2.98	2	6	159	60	2.75	2.09	30	1.55	261	2	1.36	22	260	64	<5	<20	154	0.16	<10	17	<10	12	9

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X46097	25	<0.2	6.95	5	895	<5	1.84	2	5	157	29	2.22	1.99	20	0.95	167	2	2.71	20	260	64	<5	<20	224	0.12	<10	14	<10	8	12
27	X46098	<5	0.2	6.82	15	1105	<5	1.59	2	5	182	29	2.28	1.78	20	0.73	164	8	2.74	19	230	60	<5	<20	249	0.14	<10	16	<10	11	11
28	X46099	<5	0.2	6.97	70	560	<5	1.24	3	7	132	80	3.24	2.41	50	0.48	123	1	2.01	18	180	66	10	<20	173	0.08	<10	11	<10	8	6
29	X46100	<5	<0.2	6.48	60	1020	<5	1.22	3	7	153	78	2.85	2.28	50	0.47	115	2	1.88	18	180	66	10	<20	163	0.08	<10	10	<10	8	5
30	X46101	<5	0.2	6.80	15	4000	<5	1.17	2	5	165	66	1.70	2.52	70	0.46	118	17	2.98	21	180	74	<5	<20	216	0.06	<10	12	<10	8	8
31	X46102	5	0.2	6.47	10	1515	<5	1.05	4	15	270	156	5.02	2.16	20	1.45	174	4	2.41	30	640	70	<5	<20	195	0.25	<10	63	<10	14	14
32	X46103	<5	0.2	6.38	10	2900	<5	0.88	2	9	191	138	2.68	2.27	70	0.43	104	3	2.84	22	230	66	<5	<20	215	0.08	<10	16	<10	10	7
33	X46104	<5	0.4	6.88	10	1175	<5	1.22	4	13	200	222	3.73	1.82	20	0.74	256	2	3.08	26	380	86	<5	<20	242	0.13	<10	42	<10	11	147
34	X46105	5	0.2	6.49	10	2050	<5	0.67	2	5	142	80	1.44	2.22	10	0.28	105	<1	3.33	19	110	82	<5	<20	275	0.04	<10	15	<10	3	34
QC DATA:																															
Repeat:																															
1	X46071	55	8.8	7.30	30	1225	1760	1.20	16	29	89	3517	6.65	3.04	20	0.82	616	<1	2.56	32	1480	806	45	<20	137	0.14	<10	176	<10	9	1122
7	X46077	580																													
8	X46078	250																													
10	X46080	20	0.6	6.16	15	1470	<5	1.28	3	14	232	449	3.89	2.51	40	0.88	214	1	0.75	25	290	64	10	<20	111	0.12	<10	64	<10	11	13
19	X46089	980	6.8	2.88	110	385	70	5.93	29	31	127	5565	9.64	1.62	10	2.36	993	<1	0.31	25	280	632	45	<20	121	0.04	<10	46	<10	13	2486
Resplit:																															
1	X46071	70	9.5	7.46	30	1265	1865	1.24	17	27	83	3616	6.61	2.82	20	0.87	624	<1	2.63	31	1450	860	50	<20	141	0.13	<10	178	<10	9	1144
Standard:																															
Stsd3			0.3	5.96	25	1405	<5	2.56	5	24	74	40	4.38	1.30	30	1.33	2652	7	1.12	43	1760	68	<5	<20	237	0.44	<10	135	<10	37	209
OXE74		615																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8083s
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer