Eco Tech Laboratory Ltd.
2953 Shuswap Road
Kamloops, BC
V2H 1S9 Canada
Tel + 1 250 573 5700
Fax + 1 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com

StewartGroup
Geochemical & Assay

CERTIFICATE OF ASSAY AW 2009-8065

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

21-Jul-09

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR041
Submitted by: Roger Hulstein

ET #.	Tag #		Au (g/t)	Au (oz/t)
15	X44015	*	4.73	0.138
25	X44025		2.09	0.061
26	X44026		1.02	0.030
31	X44031		1.07	0.031

QC DATA:

Standard:

Oxi67	1.87	0.055

* Based on 120g

NM/
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

All business is undertaken subject to the Company's General Conditions of Business which are available on request. Registered Office: Eco Tech Laboratory Ltd., 2953 Shuswap Road, Kamloops, BC V2H 1S9 Canada.

16-Jul-09
Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4

Phone: 250-573-5700
Fax : 250-573-4557

ICP CERTIFICATE OF ANALYSIS AW 2009-8065
Total Digest

Bushmaster Exploration
900 - 475 Howe Street
Vancouver, BC
V6C 2B3

No. of samples received: 35
Sample Type: Core
Project: Nucleus
Shipment #: 9NFR041
Submitted by: Roger Hulstein

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	X44001	15	0.2	>10	<5	350	<5	5.16	3	44	95	267	6.59	1.59	<10	3.59	865	<1	2.67	52	1040	78	<5	<20	217	0.40	<10	281	<10	19	59
2	X44002	10	<0.2	>10	25	360	<5	4.72	3	38	78	265	5.97	1.46	10	2.72	746	<1	3.09	39	1270	78	<5	<20	313	0.44	<10	261	<10	22	53
3	X44003	10	<0.2	>10	<5	355	<5	5.10	3	38	93	234	6.24	1.60	10	3.02	776	1	2.82	41	1210	78	<5	<20	264	0.39	<10	247	<10	20	50
4	X44004	25	0.2	>10	<5	500	10	4.26	3	43	70	526	7.09	2.00	10	3.12	690	<1	2.79	43	1150	80	<5	<20	232	0.42	<10	265	<10	22	52
5	X44005	65	0.4	8.72	40	385	40	5.08	3	45	180	678	7.89	2.18	10	4.45	821	<1	2.22	67	1500	78	10	<20	281	0.34	<10	262	<10	17	62
6	X44006	10	<0.2	7.58	<5	3430	<5	2.11	2	18	133	164	4.05	2.46	90	1.47	401	<1	2.56	24	590	62	<5	<20	308	0.32	<10	97	<10	20	29
7	X44007	10	<0.2	8.90	<5	485	<5	3.59	3	36	86	263	6.52	1.40	<10	2.19	882	<1	2.89	27	700	68	<5	<20	576	0.34	<10	265	<10	19	69
8	X44008 Dup	<5	<0.2	8.74	<5	485	<5	3.49	3	35	89	252	6.31	1.40	<10	2.13	839	<1	2.85	27	660	66	<5	<20	564	0.34	<10	262	<10	19	66
9	X44009	<5	<0.2	9.56	<5	560	<5	3.63	3	26	100	94	5.09	1.40	<10	1.95	762	<1	3.25	27	620	72	<5	<20	450	0.36	<10	220	<10	18	54
10	X44010	205	0.6	9.83	15	675	<5	3.02	3	29	118	327	5.72	1.68	<10	1.87	487	<1	3.08	26	570	68	<5	<20	342	0.38	<10	258	<10	17	41
11	X44011	<5	<0.2	8.01	<5	1635	<5	2.33	2	11	138	129	2.27	1.84	20	0.69	187	2	3.05	18	470	60	<5	<20	457	0.19	<10	54	<10	11	21
12	X44012	5	0.2	8.60	<5	460	<5	2.79	3	29	85	318	5.09	1.14	<10	1.48	440	<1	3.29	22	550	62	<5	<20	534	0.38	<10	193	<10	16	36
13	X44013	15	2.4	8.40	<5	255	<5	2.23	3	37	83	536	6.85	1.20	<10	1.85	545	<1	3.41	23	680	62	<5	<20	212	0.34	<10	284	<10	20	35
14	X44014	645	1.2	6.25	3155	2150	40	0.26	2	3	193	111	2.76	2.59	20	0.17	25	1	2.04	14	310	52	10	<20	284	0.10	<10	55	<10	5	6
15	X44015	>1000	2.6	6.75	4905	2250	60	0.41	2	4	118	175	3.61	2.44	10	0.34	23	<1	2.71	14	440	56	5	<20	340	0.14	<10	88	<10	6	8
16	X44016	635	1.8	6.82	1900	315	20	0.72	2	8	110	272	4.85	1.43	20	0.54	38	<1	3.23	16	560	52	<5	<20	191	0.36	<10	159	<10	11	12
17	X44017	450	1.0	6.48	3915	1045	45	0.27	2	5	111	194	4.31	2.23	20	0.32	23	<1	1.73	16	680	52	25	<20	167	0.19	<10	132	<10	7	14
18	X44018	785	1.0	7.26	1885	2970	35	0.35	2	3	101	114	3.06	1.81	10	0.23	19	<1	2.57	15	370	62	5	<20	451	0.11	<10	61	<10	7	12
19	X44019	740	0.8	7.15	5955	2315	30	0.31	2	5	120	351	4.24	2.20	20	0.37	25	<1	1.71	15	550	60	10	<20	331	0.19	<10	108	<10	8	20
20	X44020	340	0.4	6.74	2685	2455	35	0.16	2	4	109	215	5.02	2.23	20	0.21	31	<1	1.24	15	460	60	15	<20	305	0.08	<10	62	<10	7	27
21	X44021	425	1.0	6.01	990	1215	25	0.06	3	5	159	297	7.26	2.41	40	0.21	40	30	0.42	14	580	54	30	<20	100	0.08	<10	88	<10	8	35
22	X44022	770	1.4	7.99	965	750	45	0.11	2	5	108	314	4.34	2.49	20	0.57	37	<1	0.69	21	310	58	35	<20	72	0.14	<10	165	<10	7	27
23	X44023	605	2.0	8.37	1455	795	45	0.10	3	7	109	436	6.05	2.52	20	0.92	52	<1	0.49	23	640	64	15	<20	60	0.30	<10	196	<10	10	27
24	X44024	<5	<0.2	6.32	25	455	<5	0.46	1	7	138	27	1.74	4.04	40	0.22	239	4	3.10	14	240	60	<5	<20	137	0.25	<10	26	<10	20	29
25	X44025	>1000	1.4	7.27	1640	890	70	0.07	2	5	169	325	4.90	2.30	30	0.65	38	2	0.44	17	550	58	15	<20	59	0.19	<10	128	<10	10	18

ECO TECH LABORATORY LTD. **ICP CERTIFICATE OF ANALYSIS AW 2009-8065** **Bushmaster Exploration**

	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
26	X44026	>1000	1.2	6.07	2290	1020	35	0.09	2	4	205	208	4.45	2.39	30	0.47	30	<1	0.77	18	450	52	10	<20	268	0.10	<10	69	<10	7	10
27	X44027	535	0.6	7.31	3290	1220	10	0.31	2	8	211	317	3.82	2.54	20	0.78	44	<1	1.56	21	350	58	10	<20	329	0.34	<10	107	<10	13	16
28	X44028	185	<0.2	7.67	510	345	<5	0.52	2	10	214	347	3.65	1.60	20	0.77	50	<1	1.85	36	360	56	10	<20	145	0.30	<10	169	<10	12	23
29	X44029	180	<0.2	5.74	605	350	<5	0.14	2	6	156	332	5.20	1.44	30	0.46	31	<1	0.82	18	500	42	15	<20	56	0.24	<10	90	<10	13	23
30	X44030	620	<0.2	8.07	<5	110	<5	2.55	2	34	74	25	3.24	1.71	10	2.00	487	2	2.90	80	1090	82	<5	<20	346	0.45	<10	78	<10	8	40
31	X44031	>1000	0.4	6.08	4900	610	65	0.10	3	7	95	631	7.86	2.03	40	0.37	29	11	0.67	18	530	48	30	<20	54	0.22	<10	92	<10	16	29
32	X44032 Dup	920	0.8	6.13	4610	640	60	0.10	3	7	100	590	7.41	1.90	40	0.36	25	8	0.64	18	520	46	30	<20	53	0.22	<10	88	<10	14	29
33	X44033	345	0.2	8.95	120	200	15	0.90	3	18	54	739	7.94	1.39	20	1.36	210	56	1.55	33	480	66	10	20	121	0.38	<10	162	<10	24	70
34	X44034	245	0.6	6.64	155	415	15	1.15	3	32	160	1811	7.45	1.55	10	1.40	307	<1	2.14	40	370	60	10	<20	157	0.39	<10	132	<10	20	61
35	X44035	325	<0.2	7.07	385	220	5	0.47	3	17	156	1389	6.15	1.99	20	1.20	102	1	2.24	27	460	58	10	<20	140	0.26	<10	154	<10	19	55
QC DATA:																															
Repeat:																															
1	X44001	10	<0.2	>10	<5	335	<5	5.05	3	42	89	258	6.40	1.55	<10	3.44	848	<1	2.59	50	1010	76	<5	<20	212	0.39	<10	267	<10	18	56
10	X44010	175	0.4	>10	15	655	<5	2.96	3	28	109	316	5.63	1.65	<10	1.80	478	<1	3.02	25	570	68	<5	<20	332	0.40	<10	251	<10	17	41
16	X44016	590																													
19	X44019	750	0.8	6.86	5870	2260	30	0.28	2	5	115	336	4.15	2.16	20	0.35	24	<1	1.63	14	520	54	10	<20	321	0.18	<10	103	<10	8	19
21	X44021	390																													
27	X44027	570																													
Resplit:																															
1	X44001	20	<0.2	>10	<5	315	<5	4.95	3	39	91	245	6.16	1.42	<10	3.24	823	<1	2.50	50	980	76	<5	<20	205	0.35	<10	258	<10	17	53
Standard:																															
Stsd3			0.3	5.90	25	1485	<5	2.58	3	4	76	43	4.39	1.43	30	1.45	2664	7	1.19	41	1710	44	<5	<20	229	0.42	<10	132	<10	36	204
OXE74		625																													

Au: 30g FA - AA Finish
ICP : Total Digest - ICP/AES Finish
Ag : Total Digest- AA Finish

NM/nw
df/2_TD8063S
XLS/09

ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer