



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

2103 Dollarton Hwy

North Vancouver BC V7H 0A7

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: EQUITY EXPLORATION CONSULTANTS LTD.

700 - 700 WEST PENDER ST.

VANCOUVER BC V6C 1G8

Page: 1

Finalized Date: 22-SEP-2009

Account: EIAFMM

CERTIFICATE VA09098192

Project: Angie Cat

P.O. No.: FMM09-01

This report is for 35 Rock samples submitted to our lab in Vancouver, BC, Canada on 1-SEP-2009.

The following have access to data associated with this certificate:

ROBIN BLACK
ROB MCLEOD

MARTHA CLANCY

EQUITY EXPLORATION

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
PUL-31	Pulverize split to 85% <75 um
CRU-QC	Crushing QC Test
LOG-21	Sample logging - ClientBarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Ag-GRA21	Ag 30g FA-GRAV finish	WST-SIM
ME-ICP41	35 Element Aqua Regia ICP-AES	ICP-AES
ME-OG46	Ore Grade Elements - AquaRegia	ICP-AES
Pb-OG46	Ore Grade Pb - Aqua Regia	VARIABLE
Zn-OG46	Ore Grade Zn - Aqua Regia	VARIABLE

To: EQUITY EXPLORATION CONSULTANTS LTD.

ATTN: ROBIN BLACK


700 - 700 WEST PENDER ST.

VANCOUVER BC V6C 1G8


This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:


Colin Ramshaw, Vancouver Laboratory Manager



Sample Description	Method Analyte Units LOR	WEI-21	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
		Recvd Wt.	Ag	Al	As	B	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga
		kg 0.02	ppm 0.2	% 0.01	ppm 2	ppm 10	ppm 10	ppm 0.5	ppm 2	% 0.01	ppm 0.5	ppm 1	ppm 1	ppm 1	% 0.01	ppm 10
G242547		1.32	3.0	0.12	10	<10	10	<0.5	<2	0.80	648	59	1	288	2.80	<10
G242548		1.80	4.1	0.07	<2	<10	10	<0.5	3	0.32	>1000	83	1	277	2.34	10
G242549		0.78	1.8	0.35	6	<10	40	<0.5	<2	1.82	445	30	3	393	3.16	<10
G242550		0.82	1.4	0.41	9	<10	70	0.5	<2	0.15	306	21	5	224	1.72	10
G242554		2.58	0.5	0.33	3	<10	130	<0.5	3	11.70	2.1	9	4	17	2.54	<10
G242555		1.46	<0.2	0.21	3	<10	190	<0.5	<2	11.35	1.5	4	5	17	2.56	<10
G242556		2.60	0.2	0.63	8	<10	130	<0.5	<2	6.95	1.0	8	7	18	3.01	<10
G242557		0.82	<0.2	0.18	<2	<10	60	<0.5	<2	13.65	<0.5	1	3	6	2.63	<10
G242558		2.34	0.3	0.66	5	<10	300	0.5	<2	2.97	35.2	12	6	46	2.13	<10
G242559		0.56	2.5	0.14	2	<10	10	<0.5	<2	7.90	>1000	38	2	139	4.42	10
G242560		2.32	0.4	0.41	8	<10	220	<0.5	<2	7.05	14.9	8	6	37	2.96	<10
G242561		0.90	0.5	0.10	3	<10	60	<0.5	<2	12.35	5.0	1	4	6	4.00	<10
G242562		2.26	0.5	0.49	6	<10	260	0.6	<2	4.75	3.0	15	6	34	2.33	<10
G242563		0.88	<0.2	0.09	<2	<10	60	<0.5	<2	6.22	1.0	1	11	2	0.53	<10
G242564		2.68	0.5	0.52	7	<10	270	0.5	<2	4.22	2.2	13	7	35	1.87	<10
G242565		0.80	<0.2	0.15	<2	<10	100	<0.5	<2	7.31	0.7	2	9	5	0.82	<10
G242566		3.32	0.3	0.46	6	<10	240	<0.5	<2	6.45	1.5	11	6	28	2.25	<10
G242567		1.34	0.2	0.25	2	<10	100	<0.5	<2	13.15	<0.5	2	6	17	2.40	<10
G242568		2.48	0.3	0.65	2	<10	130	<0.5	<2	9.36	0.5	8	7	15	2.38	<10
G242569		1.32	<0.2	0.22	<2	<10	30	<0.5	<2	16.8	<0.5	1	4	17	2.45	<10
G090207		0.82	<0.2	0.13	<2	<10	60	<0.5	<2	5.12	48.7	6	7	10	1.57	<10
G090208		1.32	0.8	0.58	9	<10	220	<0.5	<2	6.84	5.5	11	8	36	3.03	<10
G090209		2.18	3.2	0.35	7	<10	90	<0.5	<2	5.57	188.5	17	4	126	2.49	<10
G090210		1.48	2.6	0.10	<2	<10	20	<0.5	<2	8.94	>1000	43	2	243	4.38	10
G090211		1.52	6.8	0.14	10	<10	110	<0.5	<2	0.09	8.0	2	15	228	0.43	<10
G090212		0.82	1.2	0.62	92	<10	1020	0.5	<2	0.54	8.0	13	18	142	2.22	<10
G090213		1.42	<0.2	0.05	<2	<10	30	<0.5	<2	3.06	0.5	1	13	2	0.71	<10
G090214		0.96	<0.2	0.05	<2	<10	30	<0.5	<2	2.77	0.6	1	11	1	0.49	<10
G090215		1.18	5.4	0.14	14	<10	10	<0.5	2	3.05	>1000	38	<1	619	4.02	<10
G090216		0.44	4.8	0.21	23	<10	20	<0.5	2	1.98	>1000	51	2	459	4.71	<10
G090217		0.88	<0.2	0.28	2	<10	120	<0.5	<2	5.94	4.8	9	3	17	2.53	<10
G090218		1.30	0.3	0.47	4	<10	150	<0.5	4	2.65	3.0	8	5	13	2.34	<10
G090219		1.14	<0.2	0.49	3	<10	120	0.5	<2	6.38	2.0	8	5	24	2.92	<10
B357810		0.74	>100	0.04	<2	<10	10	<0.5	3	0.05	960	46	<1	337	1.52	<10
E257861		0.96	2.9	0.09	3	<10	30	<0.5	3	13.80	1.2	3	2	1340	3.89	<10



Sample Description	Method Analyte Units LOR	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41	ME-ICP41
		Hg	K	La	Mg	Mn	Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th
		ppm 1	% 0.01	ppm 10	% 0.01	ppm 5	ppm 1	% 0.01	ppm 1	ppm 10	ppm 2	% 0.01	ppm 2	ppm 1	ppm 1	ppm 20
G242547		88	0.05	<10	0.25	119	<1	0.01	20	150	425	9.80	14	<1	20	<20
G242548		139	0.03	<10	0.05	50	<1	0.01	14	70	62	>10.0	19	<1	9	<20
G242549		53	0.06	<10	0.81	229	<1	0.02	38	140	21	3.04	10	1	47	<20
G242550		31	0.18	<10	0.08	33	<1	0.01	16	230	2720	3.64	9	1	9	<20
G242554		1	0.15	10	1.21	402	2	0.02	17	610	17	0.17	3	4	484	<20
G242555		<1	0.10	10	1.52	345	<1	0.01	14	460	29	0.05	<2	2	649	<20
G242556		1	0.17	10	1.95	446	1	0.01	21	610	8	0.13	<2	3	276	<20
G242557		<1	0.09	<10	2.24	602	<1	0.01	7	180	13	0.06	<2	2	758	<20
G242558		3	0.21	10	0.91	336	2	0.01	29	700	245	0.61	2	2	103	<20
G242559		60	0.08	<10	2.21	1470	<1	0.01	15	220	234	>10.0	10	1	232	<20
G242560		3	0.17	<10	1.66	867	1	0.01	20	690	766	0.72	3	2	319	<20
G242561		1	0.05	<10	2.85	1775	<1	0.01	6	130	490	0.60	<2	1	587	<20
G242562		<1	0.22	10	1.13	405	1	0.01	33	1060	46	0.40	<2	3	144	<20
G242563		<1	0.05	<10	0.16	210	<1	<0.01	2	90	33	0.02	<2	1	374	<20
G242564		<1	0.20	10	0.77	291	1	0.01	30	920	72	0.17	2	2	140	<20
G242565		<1	0.08	<10	0.31	261	<1	0.01	4	580	32	0.03	<2	1	459	<20
G242566		<1	0.17	10	0.94	343	<1	0.01	22	1040	25	0.15	2	2	300	<20
G242567		<1	0.04	<10	1.35	440	<1	0.01	7	180	25	0.32	<2	1	765	<20
G242568		<1	0.16	10	1.09	487	2	0.01	20	430	14	0.16	<2	2	462	<20
G242569		<1	0.03	<10	1.72	623	<1	0.01	5	70	12	<0.01	<2	1	920	<20
G090207		<1	0.06	<10	0.93	290	<1	0.01	11	360	579	0.02	<2	2	108	<20
G090208		2	0.20	10	1.32	785	1	0.01	28	1150	657	0.55	2	2	326	<20
G090209		16	0.16	<10	0.93	519	1	0.01	20	520	5890	3.19	6	2	269	<20
G090210		61	0.06	<10	2.32	1580	<1	0.01	16	280	436	9.71	11	1	290	<20
G090211		1	0.02	<10	0.01	45	1	<0.01	24	110	19	0.05	136	<1	10	<20
G090212		1	0.13	10	0.03	61	34	<0.01	234	2500	16	0.07	22	1	66	<20
G090213		<1	0.03	<10	0.31	166	<1	<0.01	2	170	6	<0.01	<2	1	136	<20
G090214		<1	0.02	<10	0.16	125	<1	<0.01	2	130	3	<0.01	<2	1	174	<20
G090215		104	0.07	<10	0.76	197	<1	0.01	47	220	89	7.56	17	<1	116	<20
G090216		100	0.09	<10	0.64	156	<1	0.01	56	290	37	5.61	15	1	51	<20
G090217		3	0.14	20	1.31	496	<1	0.02	21	410	14	0.06	<2	4	149	<20
G090218		1	0.19	20	0.81	185	2	0.03	21	800	7	0.05	2	2	98	<20
G090219		<1	0.21	20	1.33	235	1	0.03	22	2190	8	0.05	<2	4	187	<20
B357810		69	0.02	<10	0.01	18	<1	<0.01	29	40	>10000	>10.0	420	<1	8	<20
E257861		<1	0.04	<10	5.39	629	<1	0.01	6	240	216	0.06	11	2	286	<20

[illegible]