

OPERATOR: KESTREL GOLD INC.

2011 Soil Geochemistry Survey Program – DOMINION PROPERTY

DOM 173, DOM 175, DOM 177-182, DOM 207-220, DOM 242-250, DOM 276, DOM 278,
DOM 280, DOM 282, Ion 1-10, ION 11-22 Quartz Claims: Grant Numbers:
YC3119, YC 31121, YC31123-28, YC31153-66, YC31188-96, YC32722, YC32724, YC32726,
YC32728, YC75506-515, YC93780-91

**REGISTERED CLAIM OWNERS: KSL EXPLORATION (YUKON) LTD. and
BERNARD KREFT**

**Dawson Mining District, Yukon, CANADA;
NTS 115-0/15**

63° 48' North 138° 51' West

Author: Len Gal, P.Geo.

Work Performed: July 5, 2011 – January 15, 2012

Contents

Introduction	3
Property Location, Access and Physiography	3
Claim Status	3
Exploration History	7
Geology	7
Regional Geology	7
Property Geology	9
2011 Exploration Program	10
Exploration Objective	10
Procedures	10
Sample Preparation, Analysis and Security	13
2011 Soil Sampling Results	14
Gold	14
Silver	18
Arsenic	18
Lead	18
Zinc	22
Copper	22
Summary, Conclusions and Recommendations	25
Statement of Expenditures	27
Statement of Qualifications	27
References Cited	28
APPENDIX I	29
Dominion Property Claim Status	29
APPENDIX II	30
Dominion Property 2011 Soil Sample Descriptions	30
APPENDIX III	30
Dominion Property 2011 Soil Sample Analytical Results	30

Introduction

This report was written at the request of the management of Kestrel Gold Inc. It describes a soil geochemistry survey carried out at their Dominion Property, 40 km southeast of Dawson City in Yukon, Canada. The soil geochemistry survey was carried out with the objectives of: expanding previously discovered soil anomalies, expanding anomalous soil zones around previously discovered gold values in rock from trenched samples, and exploring for new soil geochemical anomalies. The over-arching goal is to discover an economic gold deposit on the property. Costs associated with the work described here are being applied for assessment work credits on the claims.

Property Location, Access and Physiography

The Dominion Property comprises 57 quartz claims with a total area of about 11.8 km² (1185 ha, 2929 acres). The property is centred about Dominion Mountain, 40 km southeast of Dawson City, Yukon. The Dominion Property is within the Dawson Mining District, covered by NTS map sheet 1150/15, and is centred at approximately latitude 63° 48' north and longitude 138° 51' west (Figures 1, 2). The property lies mainly along the divide separating the Dominion Creek and Sulphur Creek drainages.

Road access from Dawson City to the property, a distance of about 60 km, is via Yukon Highway 2 and the government-maintained Hunker Creek and Sulphur Creek roads; and the unmaintained "Upper Gold Run Road" that branches off the Sulphur Creek Road 4.0 km from the junction with Quartz Creek Road (Figures 1, 2). Upper Gold Run Road traverses the length of the property. A few overgrown roads and cat trails access other parts of the claims.

The property was unaffected by the most recent continental glaciations. It lies on the Klondike Plateau, which is characterized by low rolling hills dissected by deeply incised stream valleys. Dominion Mountain, at over 1200 m above sea level (asl) is the highest point on the property. Elevations range to a low of about 760 m asl on Caribou Creeks on the northeast margin of the property (Figure 3). The majority of the property is forested. Higher elevations are covered by mixed spruce and brush, with some sub alpine meadows on Dominion Mountain and adjacent ridges. The amount of tree cover increases at lower elevations and on south facing slopes.

The un-glaciated Klondike Plateau region experienced strong surface weathering during the early and mid-Tertiary, with the effects of surface weathering extending to depths of as much as 80 metres or more (Kreft, 2009). Regolithic material in the vicinity of the claims averages 2-3 metres in thickness. Bedrock is essentially restricted to old trenches, road cuts, and sporadic areas along the ridge northwest of Dominion Mountain. Permafrost is widespread on north facing slopes, and sporadically occurs in other areas.

Claim Status

The 57 quartz claims comprising the Dominion Property (Figure 2) are owned by KSL Exploration (Yukon) Ltd. (the DOM claims) and Bernie Kreft (the ION claims) and are subject of a 2010 option agreement with Kestrel Gold Inc. The specifics of this option agreement are beyond the scope of this report. A listing of claims and their status is attached in Appendix I.




Figure 1. Location Map of Kestrel Gold Inc. properties including Dominion (Mountain). Also shown are creeks with historic placer workings (in yellow) and mineral showings from Yukon MINFILE (grey boxes).




Figure 2. Claim map of Dominion Property, comprised of the Dom, ION and Ion claims (black outline) Yukon MINFILE occurrence 1150 062 (Brimstone) is indicated by the green dot.




Figure 3. Dominion Property showing property outline, topography, geographic features and 2011 soil sampling lines. Grid coordinates are UTM (NAD 83).

Exploration History

Significant placer gold production has occurred on Dominion Creek and Sulphur Creek which lie northeast and southwest of Dominion Property. Smaller streams such as Caribou Creek at the northeast margin of the property also have recorded placer gold production (Figure 1).

Although hard-rock exploration work in the vicinity of Dominion Mountain has been conducted since around the turn of the 20th century, the first reported work on the property wasn't until the 1987 soil sampling survey grid completed by United Keno Hill Mines. A total of 310 samples were collected, mainly along the ridge top, with values up to 603 ppb Au (McFaul, 1988). In 1996 Barramundi Resources undertook a regional stream sediment geochemistry survey that included samples from the present Dominion Property. Anomalous gold was found in streams draining the northeast side of the property (tributaries of Dominion Creek; particularly Caribou Creek; Stevens, 1997). Bernie Kreft collected a limited number of soil samples in 2008, on two widely spaced lines, which yielded values up to 79 ppb Au. In 2009 Kreft collected 142 soil samples which returned values up to 141 ppb Au. Also in 2009, Kreft excavated seven trenches to bedrock and collected 80 rock samples. Rock sample geochemistry yielded up to 2.38 g/t Au over 1.3 m in Trench #3 and 5.48 g/t Au over 0.15 m in Trench #7 (Kreft, 2009). In 2010, Bernie Kreft collected 69 soil samples on Dominion Property, with Au values up to 450 ppb (Kreft, unpublished data).

The Yukon government MINFILE database locates the Brimstone occurrence (115 O 162) at the head of Brimstone Creek on the southeast margin of Dominion Property. There is no information on this showing with respect to commodities present, or exploration history or results.

In the wider region, recent discoveries such as Kinross' White Gold deposit about 75 km to the southeast, and encouraging drill results by Kaminak Gold Corporation at their Coffee Property (about 100 km to the south), have spurred exploration in the region.

Geology

Regional Geology

Descriptions of regional and property geology are taken largely from Mortensen (1996) and his collaborators (e.g., Mackenzie et al., 2007). Debicki (1985) also produced regional geology maps of the area. Figure 4 is a regional geology map.

The Dominion Property is on the southwest side of the Tintina Fault, within the Yukon-Tanana Terrane (YTT). Yukon-Tanana Terrane is composed of Proterozoic to upper Paleozoic polyphase deformed metasedimentary, metavolcanic and metaplutonic rocks. Plutonic rocks intruded episodically in the Permian, Jurassic, Cretaceous, and Tertiary periods. Intrusive events were accompanied by volcanism, especially in the Upper Jurassic to Lower Cretaceous. Tectonic deformation included subduction and accretion of the terrane. Imbricated fault slices of allochthonous Slide Mountain Terrane are interpreted to be interleaved with the YTT.

In the area south and southeast of Dawson City, the YTT is dominantly composed of two supracrustal (dominantly metasedimentary) assemblages and three metaplutonic suites. The younger supracrustal assemblage is named Klondike Schist and is of Late Permian age. Klondike Schist can be further subdivided into felsic and mafic schists and meta-clastic units.

The metaplutonic suites include the Jim Creek pluton and the Sulphur Creek orthogneiss which outcrop west of the Dominion Property. Sulphur Creek orthogneiss is a biotite-bearing orthogneiss of quartz monzonitic affinity, and may be partly coeval with certain lithologies of the Klondike Schist.

Klondike schist lithologies are interlayered on the 1-100 m scale and are pervasively foliated and recrystallized, with few primary features recognizable. The Klondike Schist forms the upper thrust slices of a stacked pile of supracrustal rocks and local intercalated slices of ultramafic rocks of probable Slide Mountain Terrane origin (Mortensen, 1996).




Figure 4. Regional geology of the Klondike area, from Mackenzie et al., 2007. DM= Dominion Mountain, KSD= King Solomon Dome.

Property Geology

Mapping by Mortensen (in Mackenzie et al., 2007) shows the Dominion Property to be underlain by Klondike Schist members, mafic schist thrust over a metaclastic unit. The thrust is shallowly west dipping and can be traced to the northwest through much of the property.

Examination of a few scattered outcrops by the author in 2011, in trenches and road cuts, confirms quartz-chlorite schist as a dominant lithology. In the Dominion Mountain area, a few outcrops were seen of very strongly foliated chlorite schist with strong carbonate and epidote

alteration, minor quartz +/- carbonate veins associated with pyrite and minor malachite. These highly strained rocks, locally displaying brecciated textures, were interpreted to be possibly associated with the major thrust fault that passes east of the peak of Dominion Mountain.

2011 Exploration Program

Exploration Objective

An economic gold deposit is the exploration target for Kestrel Gold Inc. on the Dominion Property. Lode gold mineralization in the Klondike area is generally considered to be of the orogenic type (Mackenzie et al., 2007), with gold occurring in quartz (+/- carbonate) veins, and locally in the altered wall rock adjacent to veins. From examination of mineralized veins and vein envelopes in the King Solomon Dome area north of Dominion Property, alteration typically involves increased chlorite, carbonate, epidote, sericite (muscovite), and pyrite; depending on the original rock constituents.

Detailed geochemical surveys have proven to be effective in the area, as evidenced by recent discoveries to the south at White Gold and the Coffee Property. The region is generally blanketed by deeply weathered, oxidized soils in an unglaciated, periglacial environment (Fekete, 2011). Therefore the best representation of underlying bedrock will be from relatively deeper soils. Solifluction and similar freeze-thaw mechanisms may be important agents, in this permafrost area, in the transport of certain elements from bedrock sources (B. Kreft, pers. comm., 2011).

A soil geochemistry program was devised to follow up on known geochemical anomalies on the property, and expand these zones and search for new ones. Geophysical surveys were also completed in 2011, which will be reported on separately.

Procedures

This section on sampling procedures, and the following section on sample preparation, analysis and security, are taken largely from a memorandum written by Carl Schulze, P.Geo., principal of All Terrane Mineral Exploration Services of Whitehorse, YT (All-Terrane). All-Terrane conducted the soil sampling program under the direction of management of Kestrel Gold Inc. Mr. Schulze designed and oversaw the quality assurance-quality control (QA-QC) procedures outlined here, in consultation with Kestrel management.

Soil sampling lines were spaced at 200 metre intervals, with samples collected every 50 m. Lines were oriented approximately northeast, to cross the regional northwest trend of stratigraphy (Figure 3). Sampling lines covered the central part of the property, over an area of approximately 1.1 km by 3 km, in the hanging wall of the regional thrust fault mentioned previously. Therefore the sampled area is believed to be underlain mainly by quartz-chlorite schists. Select areas were sampled at a 25 m sample spacing with a 100 m line spacing (Figure 3). These select areas focused on extending the zones of previously identified geochemical anomalies from soil or rock sampling. Two reconnaissance sample lines were extended northeast across the northern section of the property. These reconnaissance lines covered the footwall area of the regional thrust fault, thus are underlain mainly by quartz-muscovite schists. The soil sampling grid layout is shown in Figure 3.

A total of 508 soils were collected (Figure 5). Soil sampling was completed during the period July 5-14, 2011 by employees of All Terrane, under the direction of Mr. Carl Schulze, P.Geo. Sampling crew members navigated by means of handheld GPS units and compass. Sampling lines were flagged every 25 m utilizing orange flagging tape; actual sample stations were marked with orange and blue flagging displaying the respective sample number. GPS coordinates were recorded every 200 m for sample line control, and every 100 m in areas having 25 m station spacing. Soil samples were collected by means of hand operated soil augers (“dutch augers”) from the “C” soil horizon where possible. Sample depths ranged from 20 to 95 cm, averaging 44 cm. Permafrost was noted at about 20% of sample sites, primarily along north and east-facing slopes. Three duplicate samples were taken during the course of the program.

Information recorded at each sample site included: location (UTM – NAD 83), traverse line number, soil horizon, depth, slope angle, colour, presence of permafrost, vegetation type, surficial geology where determined, percent organics, date, sampler and comments, where applicable. Samples with significant coarse rock chips were also noted, to facilitate later examination of the coarse reject fraction if desired.

Where “C” horizon material was unavailable, the “B” horizon was sampled. The minimum sample weight was 0.25 kg, before drying and preparation for analysis. Samples were placed in standard “kraft” paper envelopes. Unique sample number tags supplied by Eco Tech Laboratory Ltd. (a subsidiary of Stewart Group, now an ALS Group Company) placed in the sample bag, and the sample number written on both sides of the bag with felt pen. The sample number was also written with felt pen on blue flagging tape and attached at the sample site area. Samples were transported to All-Terrane’s camp at Scribner Creek, where they were then dried as much as possible before shipping.




Figure 5. Soil sample locations (crosses) on Dominion property grid. Grid coordinates are UTM (NAD 83).

Sample Preparation, Analysis and Security

All individual soil samples in kraft bags were sealed with a locking plastic tie (“Zap Strap”); samples were then placed in labelled rice bags which were also sealed with a “Zap Strap”. The sample stream included systematic insertion of a pair of “standard” and “blank” samples at a frequency of roughly one pair per 100 field samples. Standard and blank samples are discussed below. The sealed rice bags were then transported by All-Terrane personnel and delivered directly to a Whitehorse-based preparatory lab owned by Eco Tech Laboratory Ltd., a member of the Stewart Group with ISO 17025: 2005 accreditation. The Stewart Group was recently acquired by ALS Laboratories Inc. The majority of samples were shipped from Whitehorse directly to the main Eco Tech facility in Kamloops, BC, although a few shipments underwent drying and screening in the Whitehorse prep lab prior to shipping.

At either Whitehorse or Kamloops preparatory facility, soil samples were screened to 180 μ size (minus-80 mesh). At Eco Tech’s Kamloops lab, the fine fraction then underwent gold analysis by 30-gram fire assay with inductively coupled plasma – atomic emission spectroscopy (ICP – AES) finish, providing a detection limit of 0.005 g/t Au. All samples also underwent multi-element analysis by (ICP-AES), after digestion of a sample aliquot in aqua regia. A suite of 35 elements were analyzed, consisting of: Ag, Al, As, Ba, Be, Bi, Ca, Cd, Co, Cr, Fe, Hg, K, La, Li, Mg, Mn, Mo, Na, Ni, P, Pb, S, Sb, Se, Sn, Sr, Ti, U, V, W, Y, Zn.

All-Terrane Services provided a comprehensive quality assurance – quality control (QA-QC) regimen, consisting of the use of duplicate sampling, and insertion of pairs of standard and blank samples. Standards are utilized to determine the accuracy of analysis; blanks test for any contamination from neighbouring samples during analysis. Two sets of standard samples provided by CDN Resource Laboratories of Langley, British Columbia, Canada, were utilized: standard CDN-GS-P2 had an average gold content from 30 gram fire assay of 0.214 +/- 0.020 g/t; CDN-GS-P4A, had an average gold analysis of 0.438 +/- 0.032 g/t. Two of each of these standards were inserted throughout the program.

Information from CDN Resource Laboratories website (www.cdnlabs.com) indicates that the CDN-GS-P2 standard was prepared utilizing ore from Barrick Gold Inc.’s “Carlin-style” Bald Mountain Mine in Nevada, U.S.A. The reject material was dried, crushed, pulverized and passed through a 270 mesh screen; the sample utilized the minus 270 fraction only. This was mixed for five days in a double-cone blender, with splits sent to 14 commercial laboratories for round-robin assaying. Standard deviations per individual lab varied from 0.0042 to 0.0114.

The CDN-GS-P4A standard was prepared utilizing ore from Barrick’s “Carlin-style” Cortez Hill Mine in Nevada. To prepare the standard, 42 kg of ore was combined with 730 kg of a blank, granitic rock. The reject material was prepared in the same manner as the CDN-GS-P2 blank, with splits sent to 15 commercial laboratories for round-robin assaying. Standard deviations per individual lab ranged from 0.0053 to 0.0208.

The blank samples provided by All-Terrane Services consisted of dolomitic sand commonly utilized in gardens, purchased at Canadian Tire Corporation. No analytical data is available.

The two CDN-GS-P2 samples analyzed by Eco Tech Labs returned gold values of 230 and 215 ppb respectively, within the range of 0.214 +/- 0.020 g/t provided by CDN Resource

Laboratories. The two CDN-GS-P4A samples returned values of 435 and 430 ppb gold respectively, within the range of 0.438 +/- 0.032 ppm provided by CDN Labs. This indicates a high level of analytical accuracy of the Kamloops laboratory. All four blank samples returned sub-detection (<0.005 ppb) gold values, and un-elevated values of all other elements, except for calcium and magnesium, the main elements comprising dolomite, which both exceeded 10% per volume. These indicate that the analytical procedure is clean, with individual samples free of contamination from adjacent samples in a batch. Supported by repeatability of results from the standards, the analytical results from this program may be relied upon.

Duplicate samples test for the distribution of gold at a particular site, focusing on the presence of coarse nugget-style gold. During this program, the three duplicate samples were taken at locations of background to low gold values. Gold values within both the “original” and duplicate samples ranged from <5 ppb to 10 ppb, too low to indicate a significant difference. Values of other elements showed a limited range between the two sample types. Although the population is small, results do not suggest the presence of sporadic coarse gold, thus limiting potential that values may be highly over or under-represented.

Eco-Tech Labs, as part of their in-house QA-QC regimen, reanalysed submitted samples at a rate of approximately 12%. In addition, the lab inserted their own standards at a rate of approximately 3%. These values are included in the assay certificates. Assay certificates for all soil samples collected during the program are in Appendix II.

2011 Soil Sampling Results

Assay results are listed in Appendix II. Maps of the grid with symbolically plotted Au, Ag, As, Pb, Zn, and Cu values are shown in Figures 6-11. Soil geochemistry values of these elements are discussed below.

Gold

Gold values reached a high of 90 parts per billion (ppb). The average was 7.4 ppb, calculated after reported values of <5 ppb were assigned a value of 2 ppb. The median value was 5 ppb. Standard deviation was 7.9 ppb. A threshold of 23 ppb (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 20 ppb.

In the area of previously identified anomalous gold in soil and rock samples northwest along the ridge from Dominion Mountain (Figure 6a), the current sampling program did not expand upon the existing work. This area remains as an apparent northwest-trending zone of patchy gold anomalies on the Dom 211, 213, and 250 claims mainly. This discontinuous zone stretches over 1 km in length and is about 200-300 m wide. Current sampling, some spaced at 25 m on lines 100 m apart, did not reveal any Au values over 20 ppb in this area.

About 400 m to the northeast of this previously existing zone, however, 2011 soil sampling revealed a new, apparently northwest trending anomaly, mainly on the Dom 215 claim. The anomaly is 400 m long (across three sample lines) and expressed by three samples with values over 40 ppb Au. In fact all (five) soil samples collected during the current program that yielded 31 ppb Au or greater occur in this general area (about 400 by 400 metres) around the headwaters of Caribou Creek. These samples were collected on lines spaced 200 m apart, and further work here is recommended.

A few spot anomalies of 21-30 ppb Au occur throughout the grid, mainly on the southwestern side. Perhaps significantly, on the Dom 249 claim at the head of Meadow Gulch, a sequence of 4 of 5 soil samples over a 200 m distance yielded 21-30 ppb Au.

Previously identified anomalies to the east and southeast of a peak about 1.5 km northwest along the ridge from Dominion Mountain were not expanded or replicated in current sampling. Only two samples of 21 ppb Au (or greater) occurred on the southeast half of the grid.

Figures 6 and 7 show gold in soil results from the 2011 survey, and gold in soil results from the current survey coupled with pre-2011 results (from McFaul, 1988 and Kreft, 2009).




Figure 6. Gold in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83.




Figure 7. Gold in soil sample results from 2011 survey and compiled from previous surveys (Kreft, 2009; McFaul, 1988). Grid coordinates are UTM, NAD 83.

Silver

Silver in soil values were generally very low across the grid, with over 81% of analyses reporting less than detection limit. Maximum value was 10.6 parts per million (ppm). The average was 0.17 ppm, calculated after reported values of <0.2 ppm were assigned a value of 0.1 ppm. The median value was 0.1 ppm, below detection limit. Standard deviation was 0.5 ppm. A threshold of 1.2 ppm (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 0.4 ppm.

There were a few anomalous areas (as shown on Figure 8), mainly associated with higher zinc values.

Arsenic

The maximum value was 200 ppm, which corresponded with the maximum gold value. The average was 6.8 ppm, calculated after reported values of <5 ppm were assigned a value of 2 ppm. The median value was 5 ppm, which is the analytical detection limit. Standard deviation was 11.5 ppm. A threshold of 30 ppm (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 15 ppm.

There are scattered areas of anomalous arsenic, notable of which is the small area just northwest of Dominion Mountain associated with silver and base metals. More significantly, there is a large (over 500m wide) anomalous area over 2 sample lines in the northeast part of the grid, adjacent Caribou Creek (Figure 9). This area is associated with the trace of the regional fault and the immediate footwall rocks.

Lead

The maximum value was 540 ppm. The average was 18.4 ppm, calculated after reported values of <2 ppm were assigned a value of 1 ppm. The median value was 12 ppm and standard deviation was 47.7 ppm. A threshold of 114 ppm (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 42 ppm.

There are numerous small anomalous areas (groups of 2 or 3 samples) scattered throughout the grid, particularly on the southwest side of the grid (associated with zinc), north of Dominion Mountain (associated with silver), and some associated with gold in the area of previous trenching. Most striking is an area in the extreme northeast of the grid, on the Dom 219 and 220 claims north of Caribou Creek, with consistent and locally very high lead values over two reconnaissance sample lines and 500-700m width (Figure 10). These are associated with zinc, local Ag and As, and moderately elevated Au. The bedrock here is dominantly metaclastic rocks in the footwall of the regional thrust.

In the King Solomon Dome area, north of Dominion Property, lead (as galena) is commonly present gold-bearing quartz veins. For this reason, the Pb in soil anomaly in northeast corner of the grid should be further investigated.




Figure 8. Silver in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83.




Figure 9. Arsenic in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83.




Figure 10. Lead in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83.

Zinc

The maximum value was 750 ppm. The average value was 76 ppm, the median 64 ppm, and the standard deviation was 50.5 ppm. A threshold of 177 ppm (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 147.2 ppm.

Anomalous zinc in soil areas on Dominion grid are generally contained in discrete areas (Figure 11). These are: north of Dominion Mountain (associated with Cu, Pb, Ag, and moderate Au); southwestern side of grid (associated with Pb, Ag); trenched area northwest along ridge from Dominion Mountain (associated with Pb, moderate Ag and Au); and the extreme northeast of the grid (Dom 220 claim; associated with Pb, weakly with Au and As). There is one small area (two adjacent samples) on Dom 215 claim that is strongly anomalous in Zn, Pb, Ag, Cu, and weakly anomalous in Au and As. This multi-element association warrants closer examination.

Copper

Maximum value was 170 ppm. The average value was 48 ppm, the median 42 ppm, and the standard deviation was 25.7 ppm. A threshold of 99 ppm (average plus two standard deviations) for anomalous values can be thus estimated. The 95th percentile value is 100 ppm.

Apart from the associations noted above, the strongest area of copper in soil anomalies is just north of Dominion Mountain, where 2 adjacent sample lines have anomalous copper over 300 m width (Figure 12).

Malachite was observed in outcrop by the author near the crest of Dominion Mountain at two locations.




Figure 11. Zinc in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83




Figure 12. Copper in soil sample results from 2011 survey. Grid coordinates are UTM, NAD 83

Summary, Conclusions and Recommendations

A total of 508 soil samples were collected on Dominion Property during the period July 5-14, 2011. Samples were collected on a flagged grid consisting of about 21.8 line km of largely 200 m-spaced lines (Figures 3, 5). Samples were from the “C” soil horizon in most cases. Soil samples were analysed for gold and 35 other elements at two labs.

From analysis of the geochemical data, the following interpretations and conclusions are reached:

- Existing anomalous areas outlined in previous rock and soil samples were not significantly expanded in the current geochemical survey.
- Gold in soil anomalies were found to the northeast of and parallel to historical trends, along the slopes of Dominion Ridge, at the headwaters of Caribou Creek. Gold in soil values reached a maximum of 90 ppb in the current survey (Area D, Figure 13).
- Significant areas of anomalous silver in soil were not found. However, there was a significant area of anomalous arsenic found, mainly on the Dom 217 claim at the Caribou Creek headwaters (Area B, Figure 13).
- Lead in soil values were very strong on the two reconnaissance lines spaced 200 m apart at the north end of the property, in Caribou Creek valley on the Dom 219 and 220 claims. Lead values reached a maximum of 540 ppm (Area A, Figure 13).
- Zinc in soil showed anomalous enrichment in several areas: Caribou Creek where it partly corresponded with lead (Area A, Figure 13), a spot anomaly corresponding with the newly discovered gold anomaly (Area C, Figure 13), in the area of historic trench sampling (Area E, Figure 13), at the headwaters of the east branch of Friday Gulch on the southwest side of the grid (Area F, Figure 13), and north of Dominion Mountain (with corresponding Cu anomalies, (Area G, Figure 13).
- Copper in soil anomalies were found north of Dominion Mountain (Area G, Figure 13), and a few spot anomalous values southwest of historical trenches on Dominion Ridge. Some malachite was observed in outcrop around the peak of Dominion Mountain.
- The newly outlined gold, arsenic, and base metal anomalies (particularly multi-element larger anomalies) should be followed up with further work. Areas A,B,C,D on Figure 13 are highest priority.
- The soil geochemical grid covered only the northern half of Dominion Property. The area southeast along the ridge from Dominion Mountain remains very poorly explored by modern methods.

Figure 13 is a summary and compilation map of geochemical anomalous areas (areas A-G) and targets for follow-up work. The priority areas for follow-up are the northern Pb, Zn, +/-Au, As anomalies (A,B, C on Figure 13) and the newly outlined gold anomaly (D on Figure 13). Tighter soil sampling and/or hand and mechanized trenching may be considered. Anomalies E-G are lower priority. The southern part of the property has not seen any modern exploration and warrants at least some ridge-top prospecting, and reconnaissance soil sampling.




Figure 13. Compilation of geochemically anomalous areas worthy of follow-up. Areas A, B, C, and D are higher priority; the areas E, F, and G are lower priority. See text for details. The contoured and shaded areas of 30 ppb + and 50 ppb + Au in soils are interpreted from the 2011 soil survey results and previous data.

Statement of Expenditures

Soil geochemical survey: All Terrane Mineral Exploration Services, Eco Tech Labs Ltd., ALS Labs Ltd.	\$24, 403
Report Writing: Len Gal, P.Geo.	\$3,840
Drafting, Digitizing, GIS: Luminai Drafting Ltd.	\$1,200
TOTAL	\$29,443

Statement of Qualifications

I, Len Gal, of Courtenay, British Columbia hereby certify that:

- I am a Professional Geoscientist registered in good standing of the Association of Professional Engineers and Geoscientists of British Columbia (Registration No. 110007)
- I am a graduate of the University of British Columbia, with a B.Sc. in Geology (1986).
- I am a graduate of the University of Calgary, with a M.Sc. in Geology (1990).
- I have been engaged in geological work more or less continuously since 1986, in North and South America and Australasia, both in private industry and in the public sector (Federal and Territorial agencies).
- The information in this report is based upon review of analytical results, unpublished and published reports and maps, and materials supplied by the operator.
- I visited the Dominion Property on several occasions between May and September, 2011.

Signed this _____ day of February, 2012.

Len Gal P.Geo.

References Cited

- Debicki, R.L., 1985. Bedrock geology and mineralization of the Klondike area (west), 115O/9, 10, 11, 14, 15, 16, and 116B/2, scale 1:50,000. Indian and Northern Affairs Canada, Exploration and Geological Services Division, Open File map with marginal notes.
- Fekete, M., 2011. Surface Work Performed from August 25 to December 10, 2010, on the Portland Property. Yukon Assessment Report.
- Kreft, B., 2009. Summary Report on the Ion and Dom Claims. Yukon Assessment Report.
- MacKenzie, D.J., Craw, D., Mortensen, J.K., and Liverton, T., 2007. Structure of schist in the vicinity of the Klondike goldfield, Yukon. In: Yukon Exploration and Geology 2006, D.S. Emond, L.L. Lewis and L.H. Weston (eds.), Yukon Geological Survey, p. 197-212.
- McFaul, A.J., 1988. Geological and Geochemical Exploration of the Mackay, Dominion, King Solomon Dome, Hunker Dome, Lombard, Lloyd, Lloyd II, Lloyd III, Green Gulch and Dominion Mountain grids – Hunker Summit area. Yukon Assessment Report # 92600.
- Mortensen, J.K., 1996. Geological compilation maps of the northern Stewart River map area, Klondike and Sixtymile districts (115N/15, 16; 115O/13, 14 and parts of 115O/15, 16). Scale 1:50,000. Indian and Northern Affairs Canada Open File 1996-1(G).
- Stevens, R., 1997. Stream Sediment Survey Report, 1996. A Geological and Geochemical Report for the Hunker Dome Property (4 of 5). Yukon Assessment Report # 93711.

APPENDIX I

Dominion Property Claim Status

Claim Name	Grant Number	Claim Owner	Expiry Date*	Map Number
Dom 173	YC31119	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 175	YC31121	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 177	YC31123	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 178	YC31124	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 179	YC31125	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 180	YC31126	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 181	YC31127	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 182	YC31128	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 207	YC31153	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 208	YC31154	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 209	YC31155	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 210	YC31156	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 211	YC31157	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 212	YC31158	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 213	YC31159	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 214	YC31160	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 215	YC31161	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 216	YC31162	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 217	YC31163	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 218	YC31164	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 219	YC31165	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 220	YC31166	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 242	YC31188	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 243	YC31189	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 244	YC31190	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 245	YC31191	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 246	YC31192	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 247	YC31193	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 248	YC31194	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 249	YC31195	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 250	YC31196	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 276	YC32722	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 278	YC32724	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 280	YC32726	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Dom 282	YC32728	KSL Exploration (Yukon) Limited - 100%.	25/05/2017	115O15
Ion 1	YC75506	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 2	YC75507	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 3	YC75508	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 4	YC75509	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 5	YC75510	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 6	YC75511	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 7	YC75512	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 8	YC75513	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 9	YC75514	Bernard Kreft - 100%.	25/05/2017	115O15
Ion 10	YC75515	Bernard Kreft - 100%.	25/05/2017	115O15
ION 11	YC93780	Bernard Kreft - 100%.	25/05/2017	115O15
ION 12	YC93781	Bernard Kreft - 100%.	25/05/2017	115O15

ION	13	YC93782	Bernard Kreft - 100%.	25/05/2017	115O15
ION	14	YC93783	Bernard Kreft - 100%.	25/05/2017	115O15
ION	15	YC93784	Bernard Kreft - 100%.	25/05/2017	115O15
ION	16	YC93785	Bernard Kreft - 100%.	25/05/2017	115O15
ION	17	YC93786	Bernard Kreft - 100%.	25/05/2017	115O15
ION	18	YC93787	Bernard Kreft - 100%.	25/05/2017	115O15
ION	19	YC93788	Bernard Kreft - 100%.	25/05/2017	115O15
ION	20	YC93789	Bernard Kreft - 100%.	25/05/2017	115O15
ION	21	YC93790	Bernard Kreft - 100%.	25/05/2017	115O15
ION	22	YC93791	Bernard Kreft - 100%.	25/05/2017	115O15

*upon acceptance of the value of this work program toward assessment.

APPENDIX II

Dominion Property 2011 Soil Sample Descriptions

by All Terrane Mineral Exploration Services
(as separate attachment)

APPENDIX III

Dominion Property 2011 Soil Sample Analytical Results

(as separate attachment)


APPENDIX II

[illegible]

[illegible]

[illegible]

[illegible]



APPENDIX III

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

CERTIFICATE OF ANALYSIS AW 2011-8151

Kestrel Gold Corp.
#8-46225 Rancho Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

15-Aug-11

No. of samples received: 240
Sample Type: Soil
Project: Dawson Area
Submitted by: Darwin Wreggit

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
89	S8R281062	10
90	S8R281063	5
91	S8R281064	<5
92	S8R281065	15
93	S8R281066	5
94	S8R281067	25
95	S8R281068	25
96	S8R281069	5
97	S8R281070	5
98	S8R281071	25
99	S8R281072	5
100	S8R281073	5
101	S8R281074	20
102	S8R281075	5
103	S8R281076	10
104	S8R281077	10
105	S8R281078	5
106	S8R281079	5
107	S8R281080	5
108	S8R281081	5
109	S8R281082	10
110	S8R281083	<5
111	S8R281084	15
112	S8R281085	<5
113	S8R281086	5
114	S8R281087	5
115	S8R281088	15
116	S8R281089	20
117	S8R281090	<5
118	S8R281091	5

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
119	S8R281092	10
120	S8R281093	5
121	S8R281094	<5
122	S8R281095	<5
123	S8R281096	<5
124	S8R281097	<5
125	S8R281098	<5
126	S8R281099	<5
127	S8R281100	5
128	S8R281101	<5
129	S8R281102	<5

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
211	S8R279467	5
212	S8R279468	5
213	S8R279469	<5
214	S8R279470	5
215	S8R279471	5
216	S8R279472	10
217	S8R279473	5
218	S8R279474	5
219	S8R279475	5
220	S8R279476	5
221	S8R279477	<5
222	S8R279478	10
223	S8R279479	<5
224	S8R279480	20
225	S8R279481	5
226	S8R279482	20
227	S8R279483	10
228	S8R279484	5
229	S8R279485	15
230	S8R279486	<5
231	S8R279487	5
232	S8R279488	25
233	S8R279489	70
234	S8R279490	15
235	S8R279491	5
236	S8R279492	20
237	S8R279493	5
238	S8R279494	5
239	S8R279495	25
240	S8R279496	35

PDFfill PDF Editor with Free Writer and Tools

QC DATA:

Repeat:

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8151

15-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

89	S8R281062	5
98	S8R281071	40
106	S8R281079	5
115	S8R281088	5
124	S8R281097	<5

211	S8R279467	5
221	S8R279477	<5
229	S8R279485	10
233	S8R279489	100


PDFfill PDF Editor with Free Writer and Tools

Standard:

OXK86	590
OXK68	605
OXE86	590
OXE86	605
OXK86	615
OXK86	610
OXE86	600

FA Geochem/AA Finish

NM/mb/el
 XLS/11


ECO TECH LABORATORY LTD.
 Norman Monteith
 B.C. Certified Assayer

15-Aug-11

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8151

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 240
Sample Type: Soil
Project: **Dawson Area**
Submitted by: Darwin Wreggit

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFILL PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
89	S8R281062	<0.2	1.63	10	136	<1	<5	0.24	<1	18	78	38	2.79	<5	0.02	8	16	1.23	325	1	0.02	43	340	15	<0.01	<5	3	<10	<5	12	0.08	<5	62	<5	3	50
90	S8R281063	<0.2	2.05	<5	78	<1	<5	0.46	<1	34	154	84	4.24	<5	<0.01	2	14	2.49	720	2	0.02	84	490	12	<0.01	<5	3	<10	<5	20	0.14	<5	80	<5	3	78
91	S8R281064	0.4	2.34	<5	66	<1	<5	0.36	<1	40	430	66	4.33	<5	<0.01	2	18	3.36	825	2	0.02	157	460	15	<0.01	<5	6	<10	<5	8	0.10	<5	96	<5	4	60
92	S8R281065	<0.2	1.61	5	182	<1	<5	0.34	<1	20	38	50	3.47	<5	0.02	10	14	1.18	485	2	0.03	28	560	12	<0.01	<5	5	<10	<5	16	0.07	<5	78	<5	5	70
93	S8R281066	0.2	1.59	5	198	<1	<5	0.41	<1	14	12	46	4.24	<5	0.01	6	12	1.19	890	2	0.03	13	880	9	<0.01	<5	4	<10	<5	10	0.03	<5	58	<5	6	72
94	S8R281067	<0.2	2.10	5	176	<1	5	0.37	<1	23	32	44	4.40	<5	0.01	6	16	1.44	820	2	0.03	23	560	12	<0.01	<5	5	<10	<5	14	0.10	<5	80	<5	4	78
95	S8R281068	<0.2	1.96	5	178	<1	<5	0.44	<1	22	36	56	4.31	<5	0.01	8	14	1.37	740	2	0.03	26	700	12	<0.01	<5	5	<10	<5	16	0.08	<5	80	<5	7	78
96	S8R281069	<0.2	1.62	10	198	<1	<5	0.45	<1	17	38	24	3.16	<5	0.02	10	16	0.89	460	2	0.03	24	520	15	<0.01	<5	3	<10	<5	16	0.08	<5	74	<5	4	60
97	S8R281070	0.2	1.94	5	200	<1	<5	0.36	<1	22	60	26	3.86	<5	0.01	8	16	1.50	865	2	0.03	38	590	12	<0.01	<5	5	<10	<5	14	0.06	<5	68	<5	5	82
98	S8R281071	0.2	2.04	5	192	<1	<5	0.50	<1	23	106	30	3.81	<5	0.02	8	16	1.76	725	2	0.03	53	710	12	<0.01	<5	6	<10	<5	18	0.06	<5	76	<5	6	78
99	S8R281072	0.2	1.26	10	296	<1	<5	0.59	<1	12	32	30	3.38	<5	0.02	18	12	0.49	395	2	0.04	34	820	15	<0.01	<5	4	<10	<5	32	0.09	<5	48	<5	9	62
100	S8R281073	0.2	1.62	10	298	<1	<5	0.45	<1	18	50	30	3.19	<5	0.02	10	16	1.06	495	2	0.03	53	550	12	<0.01	<5	4	<10	<5	20	0.08	<5	70	<5	5	68
101	S8R281074	0.2	1.54	5	284	<1	5	0.49	<1	17	34	22	3.21	<5	0.02	10	14	0.93	670	2	0.03	24	660	12	<0.01	<5	4	<10	<5	20	0.06	<5	62	<5	6	60
102	S8R281075	<0.2	1.76	5	232	<1	<5	0.25	<1	16	58	30	3.60	<5	0.01	12	16	1.07	435	2	0.02	31	210	12	<0.01	<5	5	<10	<5	14	0.08	<5	68	<5	8	64
103	S8R281076	<0.2	1.83	5	128	<1	<5	0.20	<1	19	56	24	3.75	<5	0.01	6	14	1.19	495	2	0.02	30	340	12	<0.01	<5	4	<10	<5	10	0.08	<5	70	<5	3	66
104	S8R281077	<0.2	1.82	5	160	<1	5	0.30	<1	22	96	26	3.73	<5	0.01	8	14	1.46	675	2	0.02	47	500	12	<0.01	<5	5	<10	<5	14	0.07	<5	70	<5	6	70
105	S8R281078	0.2	2.12	<5	122	<1	<5	0.34	<1	17	68	26	4.54	<5	0.01	6	12	1.72	875	2	0.02	40	420	12	<0.01	<5	4	<10	<5	14	0.09	<5	60	<5	6	90
106	S8R281079	<0.2	1.83	5	190	<1	5	0.36	<1	17	30	42	3.55	<5	<0.01	6	8	1.25	595	2	0.02	20	570	15	<0.01	<5	5	<10	<5	12	0.04	<5	70	<5	4	76
107	S8R281080	<0.2	1.62	10	172	<1	<5	0.13	<1	14	72	30	2.89	<5	<0.01	6	10	1.08	380	2	0.02	32	250	15	<0.01	<5	3	<10	<5	8	0.04	<5	76	<5	3	48
108	S8R281081	<0.2	2.08	5	246	<1	<5	0.31	<1	22	186	56	3.67	<5	<0.01	8	12	1.96	645	2	0.02	67	320	15	<0.01	<5	11	<10	<5	10	0.03	<5	100	<5	6	58
109	S8R281082	<0.2	1.80	5	158	<1	<5	0.31	<1	21	148	72	3.28	<5	<0.01	6	10	1.79	535	2	0.02	58	580	15	<0.01	<5	5	<10	<5	12	0.03	<5	78	<5	5	46
110	S8R281083	<0.2	1.72	<5	120	<1	<5	0.21	<1	21	182	64	2.83	<5	<0.01	4	8	1.83	530	2	0.02	67	370	12	<0.01	<5	3	<10	<5	8	0.03	<5	66	<5	4	42

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
111	S8R281084	0.2	1.92	10	174	<1	<5	0.18	<1	20	34	66	3.70	<5	<0.01	6	10	1.31	635	2	0.02	22	240	15	<0.01	<5	5	<10	<5	8	0.04	<5	84	<5	5	70
112	S8R281085	<0.2	2.24	5	156	<1	5	0.12	<1	25	34	74	4.32	<5	<0.01	6	10	1.78	725	2	0.02	25	230	15	<0.01	<5	5	<10	<5	6	0.06	<5	118	<5	2	66
113	S8R281086	0.2	1.62	10	210	<1	<5	0.16	<1	16	28	52	3.13	<5	<0.01	8	8	0.97	645	2	0.02	20	310	15	<0.01	<5	5	<10	<5	8	0.02	<5	68	<5	7	52
114	S8R281087	0.2	1.69	10	152	<1	<5	0.16	<1	25	26	70	3.70	<5	<0.01	4	8	1.20	890	2	0.02	20	310	15	<0.01	<5	11	<10	<5	6	0.01	<5	86	<5	6	48
115	S8R281088	0.4	2.09	5	104	<1	<5	0.09	<1	26	38	76	4.12	<5	<0.01	4	10	1.44	820	2	0.02	22	270	15	<0.01	<5	8	<10	<5	4	0.02	<5	122	<5	3	66
116	S8R281089	0.4	1.87	10	152	<1	<5	0.13	<1	25	16	72	4.37	<5	0.01	4	8	1.39	940	2	0.02	16	360	15	<0.01	<5	10	<10	<5	6	0.01	<5	108	<5	6	54
117	S8R281090	<0.2	2.96	5	148	<1	<5	0.22	<1	31	138	140	5.66	<5	0.01	10	12	2.70	1090	3	0.02	58	370	18	<0.01	<5	8	<10	<5	6	0.05	<5	186	<5	4	82
118	S8R281091	0.2	2.06	5	126	<1	<5	0.21	<1	23	18	96	4.18	<5	<0.01	6	10	1.57	750	2	0.02	18	390	15	<0.01	<5	6	<10	<5	8	0.03	<5	106	<5	11	68
119	S8R281092	<0.2	1.91	5	50	<1	<5	0.15	<1	24	106	64	3.81	<5	<0.01	2	8	1.91	845	2	0.02	49	620	15	<0.01	<5	4	<10	<5	4	0.04	<5	134	<5	2	46
120	S8R281093	<0.2	1.81	5	86	<1	<5	0.15	<1	22	102	74	3.15	<5	<0.01	4	10	1.58	430	2	0.02	50	350	12	<0.01	<5	3	<10	<5	6	0.04	<5	76	<5	2	50
121	S8R281094	<0.2	1.48	<5	56	<1	<5	0.15	<1	16	168	54	1.84	<5	<0.01	2	8	1.28	275	1	0.01	59	200	9	<0.01	<5	2	<10	<5	6	0.03	<5	44	<5	1	24
122	S8R281095	<0.2	1.65	<5	74	<1	<5	0.18	<1	18	190	56	2.11	<5	<0.01	2	8	1.50	375	1	0.01	79	340	9	<0.01	<5	2	<10	<5	6	0.03	<5	38	<5	2	30
123	S8R281096	<0.2	1.64	<5	54	<1	<5	0.12	<1	16	132	58	2.12	<5	<0.01	4	8	1.22	280	2	0.02	48	320	9	<0.01	<5	2	<10	<5	8	0.04	<5	46	<5	1	32
124	S8R281097	<0.2	1.22	5	112	<1	<5	0.12	<1	6	30	22	2.03	<5	<0.01	6	4	0.38	105	2	0.02	12	370	12	0.01	<5	1	<10	<5	8	0.03	<5	62	<5	2	20
125	S8R281098	<0.2	1.88	10	108	<1	<5	0.21	<1	15	32	34	3.32	<5	<0.01	4	12	0.98	425	2	0.02	17	430	12	<0.01	<5	2	<10	<5	8	0.04	<5	84	<5	2	46
126	S8R281099	<0.2	1.87	5	144	<1	<5	0.24	<1	21	50	52	3.09	<5	<0.01	6	10	1.17	520	2	0.02	26	550	12	<0.01	<5	4	<10	<5	8	0.03	<5	72	<5	4	46
127	S8R281100	<0.2	1.80	10	234	<1	<5	0.24	<1	15	38	50	2.96	<5	<0.01	10	10	0.78	445	2	0.02	26	550	12	<0.01	<5	6	<10	<5	14	0.04	<5	72	<5	9	56
128	S8R281101	0.2	1.91	5	206	<1	<5	0.34	<1	20	42	54	3.09	<5	<0.01	6	8	0.87	850	2	0.02	21	520	15	0.01	<5	3	<10	<5	12	0.02	<5	80	<5	7	42
129	S8R281102	<0.2	1.74	5	238	<1	<5	0.60	<1	16	34	38	2.70	<5	<0.01	6	10	0.97	570	2	0.02	20	550	12	0.02	<5	3	<10	<5	20	0.02	<5	66	<5	6	46

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
211	S8R279467	0.2	2.22	<5	98	<1	<5	0.26	<1	21	18	46	3.87	<5	<0.01	4	12	1.62	635	2	0.03	18	450	12	0.04	<5	3	<10	<5	10	0.04	<5	78	<5	2	70
212	S8R279468	0.2	1.87	5	154	<1	<5	0.16	<1	15	24	54	3.09	<5	<0.01	4	10	1.04	490	2	0.02	18	300	12	<0.01	<5	4	<10	<5	8	0.03	<5	62	<5	5	68
213	S8R279469	<0.2	2.11	5	160	<1	<5	0.15	<1	16	18	42	3.78	<5	<0.01	4	12	1.09	560	2	0.02	19	400	12	<0.01	<5	3	<10	<5	6	0.03	<5	72	<5	2	62
214	S8R279470	<0.2	1.85	5	124	<1	<5	0.15	<1	20	30	76	3.33	<5	<0.01	6	8	1.39	610	2	0.02	24	270	9	<0.01	<5	5	<10	<5	6	0.04	<5	74	<5	6	54
215	S8R279471	<0.2	1.97	5	70	<1	<5	0.12	<1	16	12	62	3.98	<5	<0.01	2	10	1.25	685	2	0.02	12	400	12	<0.01	<5	4	<10	<5	4	0.03	<5	76	<5	2	102
216	S8R279472	<0.2	1.93	5	128	<1	<5	0.11	<1	17	84	40	3.13	<5	<0.01	4	12	1.36	396	2	0.02	40	160	12	<0.01	<5	4	<10	<5	6	0.05	<5	82	<5	2	54
217	S8R279473	0.2	2.88	<5	156	<1	<5	0.34	<1	32	334	86	4.01	<5	<0.01	4	12	3.67	1715	2	0.02	133	490	15	<0.01	<5	15	<10	<5	8	0.03	<5	138	<5	5	48
218	S8R279474	<0.2	1.91	<5	68	<1	<5	0.18	<1	23	264	100	2.52	<5	<0.01	2	8	2.52	510	2	0.02	98	350	9	<0.01	<5	4	<10	<5	4	0.03	<5	64	<5	3	30
219	S8R279475	<0.2	1.79	5	152	<1	<5	0.18	<1	21	60	62	2.94	<5	0.01	4	8	1.42	615	2	0.02	31	210	12	<0.01	<5	4	<10	<5	6	0.03	<5	58	<5	2	48
220	S8R279476	<0.2	1.46	5	244	<1	5	0.33	<1	35	150	74	5.10	<5	<0.01	6	8	1.10	1370	2	0.03	94	500	15	<0.01	<5	22	<10	<5	10	0.02	<5	128	<5	9	66
221	S8R279477	<0.2	1.32	5	70	<1	<5	0.26	<1	20	50	36	2.21	<5	0.02	4	6	1.07	540	2	0.01	23	860	9	<0.01	<5	2	<10	<5	6	0.02	<5	26	<5	1	64
222	S8R279478	0.2	2.01	5	116	<1	<5	0.19	<1	24	134	56	3.71	<5	<0.01	4	10	1.86	1070	2	0.02	48	410	15	<0.01	<5	8	<10	<5	8	0.03	<5	108	<5	2	44
223	S8R279479	<0.2	1.74	10	152	<1	<5	0.18	<1	13	124	34	2.54	<5	<0.01	8	10	1.06	320	2	0.02	44	280	12	<0.01	<5	4	<10	<5	10	0.04	<5	60	<5	4	38
224	S8R279480	<0.2	1.54	<5	130	<1	<5	0.24	<1	15	180	46	2.12	<5	<0.01	4	8	1.62	320	1	0.01	63	440	9	<0.01	<5	3	<10	<5	10	0.02	<5	50	<5	3	30
225	S8R279481	<0.2	1.18	10	230	<1	<5	0.38	<1	10	34	28	2.17	<5	<0.01	10	10	0.58	300	1	0.02	25	720	12	<0.01	<5	3	<10	<5	18	0.04	<5	46	<5	6	46
226	S8R279482	<0.2	1.82	5	192	<1	5	0.42	<1	22	190	56	3.01	<5	<0.01	6	12	1.64	595	2	0.02	68	560	12	<0.01	<5	4	<10	<5	14	0.03	<5	66	<5	5	54
227	S8R279483	0.6	2.05	<5	256	<1	<5	0.38	<1	33	364	132	4.48	<5	0.02	4	12	2.54	2060	2	0.02	126	510	18	<0.01	<5	27	<10	<5	10	0.03	<5	120	<5	16	46
228	S8R279484	0.2	1.85	<5	74	<1	<5	0.33	<1	20	234	82	2.32	<5	<0.01	2	12	2.53	485	2	0.01	101	430	9	<0.01	<5	5	<10	<5	6	0.02	<5	48	<5	3	28
229	S8R279485	<0.2	1.48	5	228	<1	<5	0.22	<1	14	58	44	2.47	<5	0.01	8	12	0.91	435	2	0.02	33	400	15	<0.01	<5	5	<10	<5	10	0.03	<5	54	<5	7	44
230	S8R279486	0.2	3.17	5	258	<1	5	0.27	<1	44	124	102	5.93	<5	0.01	4	16	3.39	1720	3	0.03	52	450	15	<0.01	<5	20	<10	<5	10	0.06	<5	192	<5	6	68

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
231	S8R279487	<0.2	2.03	5	134	<1	<5	0.24	<1	30	50	82	4.09	<5	0.03	4	14	1.96	1045	2	0.02	25	640	12	<0.01	<5	6	<10	<5	6	0.05	<5	118	<5	3	64
232	S8R279488	1.2	2.37	10	228	<1	5	0.39	<1	36	24	134	5.13	<5	0.09	2	18	2.28	1065	2	0.02	21	780	36	<0.01	<5	13	<10	<5	8	0.10	<5	224	<5	3	144
233	S8R279489	10.6	1.82	10	280	<1	<5	0.52	<1	22	24	112	3.67	<5	0.07	4	14	1.46	540	2	0.02	19	600	132	<0.01	5	6	<10	<5	12	0.07	<5	126	<5	5	132
234	S8R279490	0.6	1.73	20	260	<1	<5	0.49	<1	15	22	48	2.97	<5	0.02	8	12	0.99	470	2	0.02	16	570	18	0.01	<5	4	<10	<5	14	0.04	<5	74	<5	8	66
235	S8R279491	0.4	1.80	10	248	<1	<5	0.38	<1	15	22	36	3.09	<5	0.02	6	12	1.05	490	2	0.02	14	580	15	0.01	<5	3	<10	<5	12	0.05	<5	88	<5	4	58
236	S8R279492	0.2	1.75	10	204	<1	<5	0.51	<1	15	16	20	3.32	<5	0.02	6	12	1.07	575	2	0.02	12	700	12	0.02	<5	3	<10	<5	14	0.04	<5	76	<5	4	62
237	S8R279493	<0.2	1.49	5	208	<1	<5	0.31	<1	13	18	12	2.34	<5	0.01	6	10	0.77	430	2	0.02	12	590	12	0.02	<5	2	<10	<5	12	0.03	<5	52	<5	3	56
238	S8R279494	<0.2	1.78	40	222	<1	<5	0.33	<1	19	30	38	4.14	<5	0.02	18	16	1.29	800	3	0.02	27	1000	21	<0.01	<5	7	<10	<5	12	0.01	<5	72	<5	8	86
239	S8R279495	<0.2	1.80	10	252	<1	<5	0.38	<1	16	10	36	3.93	<5	0.04	10	14	1.17	705	2	0.02	11	730	12	<0.01	<5	7	<10	<5	10	0.03	<5	78	<5	9	66
240	S8R279496	<0.2	1.50	25	166	<1	<5	0.27	<1	12	4	14	3.02	<5	0.07	4	12	0.81	705	2	0.02	5	830	12	<0.01	<5	3	<10	<5	6	0.05	<5	34	<5	4	70

QC DATA:

Repeat:

PDFill PDF Editor with Free Writer and Tools

203	S8R279459	0.6	1.98	75	130	<1	5	0.33	<1	18	18	48	4.44	<5	0.02	6	22	1.41	680	3	0.02	17	540	54	0.01	<5	5	<10	<5	14	0.03	<5	88	<5	6	82
211	S8R279467	0.2	2.16	5	96	<1	<5	0.20	<1	20	18	44	3.77	<5	<0.01	4	10	1.54	625	2	0.02	17	450	12	<0.01	<5	3	<10	<5	8	0.04	<5	76	<5	2	66
220	S8R279476	0.2	1.41	5	238	<1	<5	0.33	<1	34	144	72	4.97	<5	<0.01	6	6	1.06	1345	2	0.03	91	520	15	<0.01	<5	22	<10	<5	10	0.02	<5	124	<5	8	66
229	S8R279485	0.2	1.55	5	240	<1	<5	0.22	<1	14	62	46	2.60	<5	0.01	8	10	0.92	460	2	0.02	33	400	12	<0.01	<5	5	<10	<5	12	0.03	<5	58	<5	7	46
238	S8R279494	<0.2	1.80	40	210	<1	5	0.33	<1	20	28	38	3.99	<5	0.02	16	18	1.32	770	3	0.02	27	1030	21	<0.01	<5	7	<10	<5	10	0.01	<5	68	<5	7	84

Standard:

TiII3		1.8	1.14	75	38	<1	<5	0.55	<1	15	62	22	1.90	<5	0.04	12	20	0.57	310	1	0.04	32	450	18	0.01	<5	3	<10	<5	20	0.05	<5	36	<5	6	38
TiII3		1.6	1.15	80	40	<1	<5	0.52	<1	16	64	22	1.94	<5	0.04	14	22	0.61	310	1	0.04	32	440	21	0.01	<5	3	<10	<5	18	0.05	<5	38	<5	6	40
TiII3		1.4	1.10	75	34	<1	<5	0.53	<1	14	52	20	1.98	<5	0.04	12	20	0.56	305	1	0.04	31	440	21	0.01	<5	3	<10	<5	18	0.05	<5	38	<5	5	40
TiII3		1.6	1.10	80	36	<1	<5	0.56	<1	13	62	20	1.96	<5	0.02	12	16	0.59	315	1	0.03	32	460	18	0.01	<5	3	<10	<5	14	0.05	<5	38	<5	5	38
TiII3		1.6	1.12	80	36	<1	<5	0.52	<1	13	64	20	1.96	<5	0.02	12	16	0.59	310	1	0.03	32	460	18	<0.01	<5	3	<10	<5	16	0.06	<5	40	<5	6	38

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
Till3		1.4	1.06	75	34	<1	<5	0.52	<1	12	62	20	1.90	<5	0.02	12	16	0.57	315	2	0.03	31	450	18	0.01	<5	3	<10	<5	14	0.05	<5	38	<5	5	40
Till3		1.4	1.05	80	34	<1	<5	0.50	<1	12	62	20	1.91	<5	0.02	12	16	0.57	300	2	0.03	32	450	21	0.01	<5	3	<10	<5	14	0.05	<5	36	<5	5	38

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/mb
dt/1_8151AS/1_8151BS
XLS/11


ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

PDFill PDF Editor with Free Writer and Tools



CERTIFICATE OF ANALYSIS AW 2011-8152

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

17-Aug-11

No. of samples received: 245

Sample Type: Soil

Project: Dawson Area

Submitted by: All Terrane Mineral Expl.

ET #.	Tag #	Au (ppb)
1	S8R281259	5
2	S8R281260	<5
3	S8R281261	<5
4	S8R281262	<5
5	S8R281263	<5
6	S8R281264	5
7	S8R281265	5
8	S8R281266	10
9	S8R281267	5
10	S8R281268	5
11	S8R281269	10
12	S8R281270	<5
13	S8R281271	<5
14	S8R281272	<5
15	S8R281273	5
16	S8R281274	5
17	S8R281275	10
18	S8R281276	15
19	S8R281277	5
20	S8R281278	5
21	S8R281279	5
22	S8R281280	<5
23	S8R281281	15
24	S8R281282	10
25	S8R281283	5
26	S8R281284	5
27	S8R281285	10
28	S8R281286	5
29	S8R281287	5

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

60	S8R281318	10
61	S8R281319	5
62	S8R281320	5
63	S8R281321	5
64	S8R281322	5
65	S8R281323	5
66	S8R281324	10
67	S8R281325	<5
68	S8R281326	5
69	S8R281327	5
70	S8R281328	10
71	S8R281329	<5
72	S8R281330	<5
73	S8R281331	5



Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
74	S8R281332	<5
75	S8R281333	5
76	S8R281334	10
77	S8R281335	30
78	S8R281336	5
79	S8R281337	<5
80	S8R281338	5
81	S8R281339	10
82	S8R281340	<5
83	S8R281341	10
84	S8R281342	15
85	S8R281343	15
86	S8R281344	<5
87	S8R281345	<5
88	S8R281346	<5
89	S8R281347	<5
90	S8R281348	<5
91	S8R281349	<5
92	S8R281350	<5
93	S8R281351	10
94	S8R281352	10
95	S8R281353	40

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

191	S8R287946	10
192	S8R287947	5
193	S8R287948	10
194	S8R287949	5
195	S8R287950	15
196	S8R287951	15
197	S8R287952	10
198	S8R287953	10
199	S8R287954	10
200	S8R287955	10
201	S8R287956	10
202	S8R287957	10
203	S8R287958	5
204	S8R287959	5
205	S8R287960	5



Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
206	S8R287961	15
207	S8R287962	10
208	S8R287963	15
209	S8R287964	30
210	S8R287965	5
211	S8R287966	<5
212	S8R287967	<5
213	S8R287968	5
214	S8R287969	10
215	S8R287970	10
216	S8R287971	10
217	S8R287972	10
218	S8R287973	5
219	S8R287974	5
220	S8R287975	5
221	S8R287976	10
222	S8R287977	<5
223	S8R287978	5
224	S8R287979	35
225	S8R287980	15
226	S8R287981	10
227	S8R287982	15
228	S8R287983	10
229	S8R287984	5
230	S8R287985	5
231	S8R287986	10
232	S8R287987	45
233	S8R287988	15
234	S8R287989	20
235	S8R287990	15
236	S8R287991	10
237	S8R287992	5
238	S8R287993	10
239	S8R287994	15
240	S8R287995	15
241	S8R287996	5
242	S8R287997	15
243	S8R287998	5
244	S8R287999	215
245	S8R288000	<5

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

QC DATA:

Repeat:

PDFill PDF Editor with Free Writer and Tools

194	S8R287949	5
203	S8R287958	5
211	S8R287966	<5
220	S8R287975	5
229	S8R287984	10
232	S8R287987	55
238	S8R287993	15

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8152

17-Aug-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

Standard:

OXE86	620
OXE86	595
OXE86	600
OXE86	620
OXE86	600
OXE86	595
OXE86	610

FA Geochem/AA Finish

NM/sa
XLS/11


ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

PDFfill PDF Editor with Free Writer and Tools

17-Aug-11

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8152

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 245
Sample Type: Soil
Project: Dawson Area
Submitted by: All Terrane Mineral Expl.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zr
60	S8R281318	<0.2	2.21	5	166	<1	<5	0.21	<1	25	18	58	4.12	<5	0.10	4	16	1.36	530	1	0.03	15	330	12	<0.01	<5	3	<10	<5	10	0.12	<5	98	<5	2	64
61	S8R281319	<0.2	1.47	10	202	<1	<5	0.27	<1	13	26	34	2.86	<5	0.05	10	14	0.63	350	1	0.03	20	520	12	<0.01	<5	4	<10	<5	16	0.07	<5	62	<5	7	58
62	S8R281320	<0.2	1.31	10	240	<1	<5	0.42	<1	13	28	34	2.66	<5	0.04	8	12	0.61	405	1	0.03	22	610	12	<0.01	<5	4	<10	<5	18	0.06	<5	54	<5	8	56
63	S8R281321	<0.2	1.62	10	258	<1	<5	0.43	<1	17	40	36	3.07	<5	0.04	10	12	0.88	495	1	0.03	26	710	12	<0.01	<5	5	<10	<5	16	0.05	<5	60	<5	8	64
64	S8R281322	<0.2	1.47	10	294	<1	<5	0.48	<1	13	24	32	2.57	<5	0.04	8	14	0.62	395	1	0.03	20	540	12	<0.01	<5	3	<10	<5	18	0.05	<5	56	<5	7	56
65	S8R281323	<0.2	1.40	10	270	<1	<5	0.65	<1	15	22	36	2.76	<5	0.04	6	12	0.68	495	1	0.03	18	620	12	0.02	<5	3	<10	<5	20	0.04	<5	52	<5	6	56
66	S8R281324	<0.2	1.43	5	260	<1	<5	0.73	<1	14	34	34	2.43	<5	0.04	6	12	0.79	540	<1	0.02	23	600	12	0.02	<5	4	<10	<5	20	0.04	<5	52	<5	6	54
67	S8R281325	<0.2	1.53	5	166	<1	<5	0.89	<1	19	58	36	2.75	<5	0.03	2	10	1.34	540	<1	0.02	33	670	9	0.02	<5	4	<10	<5	20	0.03	<5	60	<5	4	48
68	S8R281326	<0.2	1.51	5	210	<1	<5	0.70	<1	16	54	34	2.43	<5	0.03	4	12	1.01	425	<1	0.02	30	600	9	0.02	<5	4	<10	<5	20	0.03	<5	56	<5	5	48
69	S8R281327	<0.2	1.78	<5	138	<1	<5	0.23	<1	19	166	60	2.44	<5	0.02	4	12	1.57	365	<1	0.02	67	350	9	<0.01	<5	3	<10	<5	8	0.04	<5	54	<5	3	42
70	S8R281328	<0.2	1.83	10	156	<1	<5	0.27	<1	17	98	46	2.59	<5	0.03	4	14	1.08	275	1	0.02	43	400	12	<0.01	<5	3	<10	<5	12	0.06	<5	60	<5	3	44

PDFILL PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
71	S8R281329	<0.2	1.58	<5	84	<1	<5	0.26	<1	20	128	58	2.36	<5	0.02	2	10	1.38	315	<1	0.02	55	480	9	<0.01	<5	2	<10	<5	8	0.05	<5	50	<5	2	36
72	S8R281330	<0.2	1.42	5	190	<1	<5	0.44	<1	15	24	44	2.66	<5	0.04	6	10	0.87	370	<1	0.03	19	660	9	<0.01	<5	4	<10	<5	14	0.05	<5	66	<5	6	46
73	S8R281331	<0.2	1.76	25	204	<1	<5	0.48	<1	22	30	56	3.33	<5	0.03	4	12	1.14	620	1	0.04	28	610	12	0.03	<5	5	<10	<5	16	0.04	<5	78	<5	7	56
74	S8R281332	<0.2	1.75	5	186	<1	<5	0.66	<1	19	24	52	3.16	<5	0.03	4	12	1.22	635	1	0.03	17	490	9	0.02	<5	4	<10	<5	18	0.07	<5	92	<5	5	50
75	S8R281333	<0.2	1.90	10	128	<1	<5	0.14	<1	18	30	54	3.44	<5	0.03	8	14	0.95	350	1	0.03	22	200	12	<0.01	<5	5	<10	<5	8	0.06	<5	84	<5	5	56
76	S8R281334	<0.2	1.61	10	122	<1	<5	0.13	<1	12	18	22	3.10	<5	0.03	6	12	0.65	265	1	0.03	12	380	12	<0.01	<5	2	<10	<5	8	0.07	<5	78	<5	2	44
77	S8R281335	<0.2	1.51	10	96	<1	<5	0.13	<1	10	18	20	3.05	<5	0.04	4	14	0.55	290	1	0.03	9	470	12	<0.01	<5	2	<10	<5	8	0.07	<5	68	<5	2	40
78	S8R281336	<0.2	1.39	10	124	<1	<5	0.13	<1	9	14	22	2.54	<5	0.10	8	10	0.53	385	<1	0.02	9	470	12	<0.01	<5	4	<10	<5	6	0.05	<5	46	<5	7	48
79	S8R281337	<0.2	1.99	5	86	<1	<5	0.12	<1	18	18	26	4.18	<5	0.04	4	12	1.14	485	2	0.03	10	490	12	<0.01	<5	3	<10	<5	8	0.15	<5	94	<5	2	52
80	S8R281338	<0.2	2.26	10	128	<1	<5	0.15	<1	25	20	40	4.02	<5	0.04	6	14	1.29	510	1	0.03	14	280	12	<0.01	<5	3	<10	<5	8	0.12	<5	92	<5	3	56
81	S8R281339	<0.2	1.55	60	108	<1	<5	0.27	<1	17	14	32	3.19	<5	0.05	4	14	0.93	725	<1	0.03	11	610	12	<0.01	<5	3	<10	<5	8	0.02	<5	56	<5	5	60
82	S8R281340	<0.2	1.86	10	208	<1	<5	0.22	<1	15	30	38	3.36	<5	0.04	8	14	0.70	365	1	0.03	21	300	12	<0.01	<5	8	<10	<5	10	0.03	<5	82	<5	7	52
83	S8R281341	<0.2	1.89	5	106	<1	<5	0.17	<1	20	14	36	3.65	<5	0.03	4	10	1.24	445	1	0.03	12	310	9	0.01	<5	5	<10	<5	8	0.03	<5	90	<5	4	48
84	S8R281342	<0.2	2.00	10	96	<1	<5	0.13	<1	29	18	52	4.06	<5	0.03	4	14	1.24	465	1	0.03	15	310	9	<0.01	<5	4	<10	<5	6	0.04	<5	82	<5	3	52
85	S8R281343	<0.2	2.26	10	170	<1	<5	0.14	<1	18	28	42	3.64	<5	0.03	6	18	0.91	330	2	0.03	20	230	15	<0.01	<5	6	<10	<5	8	0.05	<5	78	<5	4	50
86	S8R281344	<0.2	1.80	10	156	<1	<5	0.14	<1	12	24	24	2.99	<5	0.03	6	16	0.63	200	1	0.03	16	330	12	<0.01	<5	4	<10	<5	8	0.04	<5	70	<5	3	40
87	S8R281345	<0.2	1.76	<5	60	<1	<5	0.13	<1	22	98	84	2.99	<5	0.02	2	14	1.45	380	1	0.02	47	230	9	<0.01	<5	3	<10	<5	6	0.07	<5	70	<5	2	36
88	S8R281346	<0.2	1.54	10	90	<1	<5	0.11	<1	14	32	26	2.88	<5	0.04	6	12	0.57	295	2	0.03	14	290	12	<0.01	<5	2	<10	<5	8	0.10	<5	82	<5	2	42
89	S8R281347	<0.2	1.90	5	98	<1	<5	0.15	<1	19	56	44	3.31	<5	0.02	4	14	1.29	345	1	0.03	31	220	12	<0.01	<5	4	<10	<5	8	0.09	<5	90	<5	3	46
90	S8R281348	<0.2	1.90	5	94	<1	<5	0.19	<1	24	76	66	2.97	<5	0.03	4	12	1.54	440	<1	0.03	45	370	9	<0.01	<5	3	<10	<5	10	0.06	<5	62	<5	2	46
91	S8R281349	<0.2	1.83	5	126	<1	<5	0.16	<1	19	108	42	2.72	<5	0.02	6	12	1.16	330	1	0.03	47	260	12	<0.01	<5	3	<10	<5	10	0.07	<5	62	<5	4	44
92	S8R281350	<0.2	1.49	<5	56	<1	<5	0.20	<1	19	126	50	2.11	<5	0.02	2	10	1.32	310	<1	0.02	54	400	6	<0.01	<5	2	<10	<5	8	0.05	<5	42	<5	2	36
93	S8R281351	<0.2	1.57	5	130	<1	<5	0.20	<1	12	36	40	2.48	<5	0.03	4	10	0.76	255	1	0.03	19	450	27	0.01	<5	<1	<10	<5	10	0.03	<5	56	<5	3	60
94	S8R281352	<0.2	1.89	5	160	<1	<5	0.28	<1	17	32	44	3.12	<5	0.02	6	12	1.10	435	1	0.03	20	330	15	<0.01	<5	5	<10	<5	8	0.04	<5	74	<5	4	70
95	S8R281353	<0.2	1.74	5	186	<1	<5	0.26	<1	16	22	46	2.89	<5	0.03	6	12	0.95	405	1	0.03	17	460	12	<0.01	<5	3	<10	<5	10	0.03	<5	68	<5	4	52

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zr
111	68D087866	0.0	1.00	10	0.70	1	5	0.00	1	10	10	00	0.05	5	0.10	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00

PDFILL PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
454	000007000																																			

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
191	S8R287946	<0.2	1.37	10	258	<1	<5	0.46	<1	13	14	18	2.52	<5	0.04	8	12	0.87	440	<1	0.03	12	620	18	0.02	<5	3	<10	<5	14	0.02	<5	52	<5	5	54
192	S8R287947	<0.2	1.75	15	374	<1	<5	0.48	<1	15	30	24	2.93	<5	0.03	12	12	0.89	365	1	0.03	22	540	18	0.03	<5	2	<10	<5	22	0.02	<5	50	<5	6	66
193	S8R287948	0.2	2.00	30	154	<1	<5	0.58	<1	18	48	44	3.62	<5	0.04	26	18	1.24	510	2	0.04	39	900	21	0.03	<5	3	<10	<5	14	<0.01	<5	40	<5	12	92
194	S8R287949	<0.2	1.87	20	350	<1	<5	0.27	<1	15	36	26	2.98	<5	0.04	20	18	0.79	680	2	0.03	24	570	18	<0.01	<5	3	<10	<5	12	0.03	<5	54	<5	8	68
195	S8R287950	<0.2	1.03	15	286	<1	<5	0.16	<1	7	16	20	2.03	<5	0.07	36	8	0.30	165	1	0.02	14	410	42	<0.01	<5	2	<10	<5	10	0.04	<5	30	<5	8	62
196	S8R287951	<0.2	1.31	10	808	<1	<5	0.23	<1	9	22	22	2.26	<5	0.08	30	10	0.37	220	1	0.03	16	280	54	<0.01	<5	4	<10	<5	16	0.05	<5	46	<5	10	52
197	S8R287952	<0.2	1.02	10	276	<1	<5	0.17	<1	7	16	16	2.04	<5	0.08	50	8	0.26	150	1	0.02	11	250	48	<0.01	<5	3	<10	<5	12	0.03	<5	32	<5	16	52
198	S8R287953	<0.2	1.16	10	476	<1	<5	0.24	<1	7	18	20	2.22	<5	0.09	36	8	0.34	170	1	0.03	14	360	24	<0.01	<5	4	<10	<5	14	0.05	<5	40	<5	15	54
199	S8R287954	<0.2	1.32	10	340	<1	<5	0.18	<1	7	18	18	2.08	<5	0.07	26	8	0.26	145	1	0.03	12	380	27	<0.01	<5	2	<10	<5	12	0.03	<5	38	<5	8	36
200	S8R287955	0.2	1.08	5	606	<1	<5	0.35	<1	11	14	12	1.67	<5	0.05	30	10	0.37	215	1	0.02	11	460	27	0.03	<5	2	<10	<5	16	0.02	<5	32	<5	14	40
201	S8R287956	<0.2	1.33	10	388	<1	<5	0.22	<1	9	22	20	2.21	<5	0.05	22	10	0.49	170	1	0.03	16	490	66	<0.01	<5	3	<10	<5	12	0.05	<5	46	<5	6	68
202	S8R287957	<0.2	1.14	10	292	<1	<5	0.19	<1	7	18	14	1.83	<5	0.05	22	10	0.44	120	1	0.02	12	420	90	<0.01	<5	2	<10	<5	10	0.05	<5	42	<5	4	58
203	S8R287958	<0.2	1.08	15	332	<1	<5	0.10	<1	5	14	10	2.13	<5	0.07	32	6	0.23	165	2	0.02	7	340	138	<0.01	<5	2	<10	<5	6	0.03	<5	46	<5	4	48
204	S8R287959	<0.2	1.67	10	460	<1	<5	0.15	<1	10	30	22	2.47	<5	0.04	30	14	0.75	185	2	0.03	21	210	120	<0.01	<5	4	<10	<5	10	0.05	<5	54	<5	5	148
205	S8R287960	<0.2	1.79	10	406	<1	<5	0.21	<1	10	24	38	2.95	<5	0.04	14	12	0.87	205	2	0.03	21	470	465	<0.01	<5	4	<10	<5	10	0.06	<5	64	<5	3	260
206	S8R287961	0.4	1.96	20	358	<1	<5	0.10	<1	10	22	32	3.32	<5	0.05	14	16	0.47	195	2	0.03	20	200	468	<0.01	<5	3	<10	<5	8	0.06	<5	64	<5	2	70
207	S8R287962	<0.2	1.94	15	342	<1	<5	0.09	<1	11	36	32	3.29	<5	0.05	20	14	0.56	220	2	0.03	23	140	327	<0.01	<5	6	<10	<5	8	0.07	<5	66	<5	9	96
208	S8R287963	0.4	1.43	10	246	<1	<5	0.07	<1	7	26	44	2.62	<5	0.05	20	10	0.39	155	3	0.03	13	150	540	0.02	<5	2	<10	<5	6	0.05	<5	52	<5	3	114
209	S8R287964	0.4	0.82	5	220	<1	<5	0.05	<1	4	12	28	2.20	<5	0.04	18	6	0.17	75	4	0.02	7	170	456	0.02	<5	1	<10	<5	4	0.02	<5	26	<5	2	66
210	S8R287965	<0.2	1.30	10	546	<1	<5	0.23	<1	8	20	12	2.18	<5	0.05	22	10	0.43	250	1	0.03	12	350	39	<0.01	<5	3	<10	<5	12	0.05	<5	46	<5	5	50
211	S8R287966	<0.2	1.12	5	464	<1	<5	0.16	<1	9	18	18	1.93	<5	0.04	24	8	0.42	220	1	0.02	14	210	45	<0.01	<5	3	<10	<5	10	0.06	<5	40	<5	6	62
212	S8R287967	<0.2	1.24	5	322	<1	<5	0.18	<1	8	20	16	1.96	<5	0.04	16	8	0.60	180	1	0.02	16	330	105	<0.01	<5	2	<10	<5	8	0.05	<5	40	<5	4	100
213	S8R287968	<0.2	1.19	5	362	<1	<5	0.15	<1	7	20	24	1.93	<5	0.03	24	10	0.53	190	1	0.02	14	210	111	<0.01	<5	3	<10	<5	8	0.04	<5	36	<5	7	110
214	S8R287969	<0.2	1.35	10	412	<1	<5	0.16	<1	9	22	24	2.32	<5	0.04	20	10	0.58	220	2	0.02	17	290	117	<0.01	<5	3	<10	<5	10	0.04	<5	46	<5	4	168
215	S8R287970	<0.2	1.48	10	530	<1	<5	0.22	<1	11	24	30	2.58	<5	0.05	18	10	0.52	280	2	0.02	18	430	153	<0.01	<5	4	<10	<5	12	0.06	<5	54	<5	5	136
216	S8R287971	<0.2	1.49	10	556	<1	<5	0.26	<1	11	26	30	2.59	<5	0.04	18	12	0.51	305	2	0.03	19	410	144	<0.01	<5	4	<10	<5	14	0.06	<5	54	<5	7	90
217	S8R287972	<0.2	1.54	10	640	<1	<5	0.28	<1	11	26	32	2.65	<5	0.04	22	12	0.51	265	2	0.03	19	420	156	<0.01	<5	4	<10	<5	16	0.06	<5	56	<5	8	88
218	S8R287973	<0.2	1.43	10	500	<1	<5	0.27	<1	10	24	26	2.38	<5	0.04	20	10	0.50	220	2	0.02	17	500	123	<0.01	<5	3	<10	<5	14	0.05	<5	50	<5	6	98
219	S8R287974	<0.2	1.51	10	410	<1	<5	0.41	<1	18	26	20	2.89	<5	0.04	14	14	0.86	820	1	0.03	20	600	24	0.05	<5	4	<10	<5	24	0.03	<5	52	<5	10	70
220	S8R287975	<0.2	1.53	20	216	<1	<5	0.33	<1	13	28	18	3.17	<5	0.04	12	14	0.81	380	1	0.03	19	650	18	0.04	<5	3	<10	<5	18	0.03	<5	60	<5	6	58
221	S8R287976	<0.2	1.39	15	202	<1	<5	0.27	<1	12	40	22	2.83	<5	0.04	14	12	0.73	220	1	0.03	27	630	18	0.01	<5	3	<10	<5	14	0.04	<5	54	<5	5	54
222	S8R287977	<0.2	1.21	20	310	<1	<5	0.41	<1	11	36	22	2.59	<5	0.04	14	10	0.70	250	1	0.03	25	660	15	0.03	<5	3	<10	<5	22	0.04	<5	52	<5	7	50
223	S8R287978	<0.2	1.37	15	158	<1	<5	0.41	<1	23	62	16	2.98	<5	0.03	8	10	1.37	1970	1	0.02	44	740	12	0.01	<5	4	<10	<5	14	0.02	<5	64	<5	3	54
224	S8R287979	3.8	1.18	95	362	<1	<5	0.93	<1	49	24	34	6.47	<5	0.03	6	10	0.73	3525	2	0.05	35	750	30	0.05	<5	3	<10	<5	34	0.02	<5	52	<5	5	60
225	S8R287980	<0.2	1.28	35	210	<1	<5	0.65	<1	14	28	32	2.94	<5	0.04	10	12	0.86	260	1	0.03	21	540	30	0.03	<5	4	<10	<5	22	0.03	<5	48	<5	7	70
226	S8R287981	<0.2	1.30	20	226	<1	<5	0.65	<1	13	24	28	2.75	<5	0.04	10	10	0.90	390	1	0.03	19	480	18	0.03	<5	3	<10	<5	20	0.02	<5	50	<5	8	58
227	S8R287982	<0.2	1.46	75	264	<1	<5	0.41	<1	15	16	20	3.10	<5	0.04	10	14	0.83	420	1	0.03	13	580	24	0.02	<5	4	<10	<5	14	0.03	<5	54	<5	6	62
228	S8R287983	<0.2	1.37	10	270	<1	<5	0.58	<1	15	16	20	2.99	<5	0.04	8	12	0.97	535	1	0.03	11	510	18	0.03	<5	3	<10	<5	16	0.03	<5	58	<5	6	58
229	S8R287984	<0.2	1.38	15	302	<1	<5	0.88	<1	16	16	22	2.91	<5	0.05	8	10	0.99	820	1	0.03	11	640	15	0.04	<5	3	<10	<5	22	0.03	<5	52	<5	8	56
230	S8R287985	<0.2	1.71	30	286	<1	<5	1.01	<1	21	22	36	3.67	<5	0.04	8	12	1.32	885	1	0.03	15	550	15	0.05	<5	5	<10	<5	24	0.04	<5	76	<5	7	

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
231	S8R287986	<0.2	1.77	20	236	<1	<5	0.61	<1	19	20	42	3.46	<5	0.05	8	12	1.41	805	1	0.03	15	630	15	0.02	<5	6	<10	<5	14	0.03	<5	68	<5	9	62
232	S8R287987	<0.2	1.77	30	220	<1	<5	0.46	<1	20	22	48	3.74	<5	0.05	8	12	1.37	585	<1	0.03	16	600	12	0.01	<5	6	<10	<5	12	0.03	<5	78	<5	8	56
233	S8R287988	<0.2	1.85	25	212	<1	<5	0.35	<1	21	20	42	4.00	<5	0.09	8	14	1.46	610	1	0.03	16	540	12	<0.01	<5	5	<10	<5	10	0.05	<5	84	<5	5	62
234	S8R287989	<0.2	1.18	5	114	<1	<5	0.71	<1	15	22	24	2.58	<5	0.02	6	8	0.85	390	1	0.02	15	400	12	0.03	<5	3	<10	<5	12	0.02	<5	42	<5	3	54
235	S8R287990	<0.2	2.04	10	184	<1	<5	0.28	<1	21	38	46	4.09	<5	0.02	10	12	1.40	675	1	0.03	26	330	18	<0.01	<5	6	<10	<5	8	0.03	<5	70	<5	6	68
236	S8R287991	<0.2	2.09	5	142	<1	<5	0.29	<1	20	38	46	4.04	<5	0.02	6	14	1.45	685	2	0.03	25	350	15	<0.01	<5	5	<10	<5	8	0.03	<5	70	<5	4	68
237	S8R287992	<0.2	1.83	10	146	<1	<5	0.17	<1	15	40	36	3.38	<5	0.02	8	12	1.06	370	2	0.02	23	290	18	<0.01	<5	4	<10	<5	8	0.04	<5	70	<5	3	66
238	S8R287993	<0.2	2.33	5	152	<1	<5	0.19	<1	29	56	82	5.01	<5	0.01	10	12	1.83	965	1	0.03	35	430	18	<0.01	<5	9	<10	<5	6	0.02	<5	88	<5	8	68
239	S8R287994	<0.2	1.88	5	142	<1	<5	0.56	<1	30	48	58	4.16	<5	0.02	6	10	1.53	1305	1	0.03	29	560	15	0.02	<5	5	<10	<5	12	0.02	<5	72	<5	6	52
240	S8R287995	<0.2	1.31	5	124	<1	<5	0.57	<1	12	18	26	2.33	<5	0.02	6	8	0.81	440	1	0.02	13	520	12	0.03	<5	1	<10	<5	12	0.02	<5	42	<5	3	42
241	S8R287996	<0.2	2.45	5	88	<1	<5	0.14	<1	25	44	64	4.71	<5	0.02	6	12	1.83	790	2	0.03	26	380	15	<0.01	<5	6	<10	<5	6	0.05	<5	108	<5	3	56
242	S8R287997	<0.2	1.72	10	80	<1	<5	0.09	<1	13	24	32	3.34	<5	0.02	8	10	0.82	310	1	0.02	13	490	18	<0.01	<5	3	<10	<5	6	0.05	<5	70	<5	2	58
243	S8R287998	<0.2	1.38	10	194	<1	<5	0.22	<1	13	22	20	2.81	<5	0.03	14	10	0.72	380	1	0.03	16	490	15	<0.01	<5	3	<10	<5	12	0.06	<5	52	<5	6	48
244	S8R287999	<0.2	0.17	480	1174	<1	<5	1.16	<1	3	22	62	4.07	<5	0.07	2	2	0.03	105	18	0.03	17	50	18	0.13	30	<1	<10	<5	26	0.01	<5	12	<5	2	16
245	S8R288000	<0.2	0.12	<5	22	<1	<5	>10	<1	1	<2	<2	0.40	<5	0.09	<2	4	>10	175	<1	0.01	3	160	<3	0.10	<5	<1	<10	<5	30	<0.01	<5	2	<5	<1	14

QC DATA:**Repeat:**

63	S8R281321	<0.2	1.59	10	256	<1	<5	0.42	<1	17	40	36	3.05	<5	0.04	10	12	0.88	510	1	0.03	26	690	12	<0.01	<5	5	<10	<5	16	0.05	<5	60	<5	8	64
71	S8R281329	<0.2	1.54	<5	84	<1	<5	0.24	<1	20	122	56	2.29	<5	0.02	2	10	1.35	305	<1	0.02	53	460	6	<0.01	<5	2	<10	<5	8	0.04	<5	48	<5	2	34
80	S8R281338	<0.2	2.20	10	128	<1	<5	0.14	<1	26	20	38	3.86	<5	0.03	6	14	1.21	510	1	0.03	14	260	12	<0.01	<5	3	<10	<5	8	0.11	<5	90	<5	2	56
89	S8R281347	<0.2	1.91	5	98	<1	<5	0.15	<1	19	56	44	3.27	<5	0.02	4	14	1.25	350	1	0.03	31	220	12	<0.01	<5	4	<10	<5	8	0.09	<5	88	<5	3	46

194	S8R287949	<0.2	1.76	20	334	<1	<5	0.25	<1	14	34	24	2.86	<5	0.04	18	16	0.76	655	2	0.03	23	540	18	<0.01	<5	3	<10	<5	12	0.03	<5	52	<5	8	66
203	S8R287958	<0.2	1.07	15	324	<1	<5	0.10	<1	5	14	10	2.07	<5	0.07	30	6	0.22	165	2	0.02	7	340	135	<0.01	<5	2	<10	<5	6	0.03	<5	46	<5	4	46
211	S8R287966	<0.2	1.15	5	484	<1	<5	0.16	<1	9	18	18	2.05	<5	0.04	24	8	0.45	230	1	0.02	15	200	48	<0.01	<5	3	<10	<5	10	0.06	<5	42	<5	6	62
220	S8R287975	<0.2	1.53	20	216	<1	<5	0.33	<1	12	30	18	3.26	<5	0.04	12	14	0.84	365	2	0.03	18	630	21	0.04	<5	3	<10	<5	18	0.03	<5	60	<5	6	58
229	S8R287984	<0.2	1.36	15	298	<1	<5	0.86	<1	16	16	22	2.88	<5	0.05	8	10	1.01	800	1	0.03	11	630	15	0.04	<5	3	<10	<5	22	0.03	<5	52	<5	8	56
238	S8R287993	<0.2	2.32	10	156	<1	<5	0.19	<1	28	56	82	4.84	<5	0.02	10	12	1.69	960	2	0.03	34	420	18	<0.01	<5	9	<10	<5	6	0.02	<5	86	<5	9	68

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
Standard:																																				
Till3		1.5	1.05	75	38	<1	<5	0.58	<1	14	62	22	2.00	<5	0.08	12	18	0.58	295	<1	0.04	31	450	18	0.01	<5	3	<10	<5	16	0.07	<5	36	<5	6	40
Till3		1.4	1.09	80	40	<1	<5	0.55	<1	15	62	22	2.02	<5	0.08	14	18	0.61	310	<1	0.04	31	450	21	0.01	<5	3	<10	<5	14	0.07	<5	38	<5	6	38
Till3		1.4	1.08	85	38	<1	<5	0.55	<1	14	62	22	1.92	<5	0.08	12	18	0.57	310	1	0.04	31	440	21	0.01	<5	3	<10	<5	14	0.07	<5	38	<5	6	38
Till3		1.6	1.11	85	36	<1	<5	0.56	<1	15	60	22	1.98	<5	0.08	14	18	0.58	320	1	0.03	31	440	21	<0.01	<5	3	<10	<5	14	0.07	<5	36	<5	6	44
Till3		1.4	1.12	80	40	<1	<5	0.57	<1	15	60	22	1.93	<5	0.07	16	18	0.61	310	1	0.04	30	450	21	0.01	<5	3	<10	<5	14	0.08	<5	38	<5	6	38
Till3		1.4	1.11	85	40	<1	<5	0.57	<1	15	62	20	2.06	<5	0.07	16	16	0.60	310	1	0.04	31	430	18	0.01	<5	3	<10	<5	14	0.08	<5	36	<5	6	42
Till3		1.4	1.09	85	36	<1	<5	0.57	<1	15	64	20	2.04	<5	0.07	16	16	0.62	310	1	0.03	31	450	18	0.01	<5	3	<10	<5	14	0.08	<5	38	<5	6	46

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/sa

dt/2_8150CS/2_8152BS/2_8152CS

XLS/11



ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

PDFill PDF Editor with Free Writer and Tools



CERTIFICATE OF ANALYSIS AW 2011-8166

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

21-Sep-11

No. of samples received: 212

Sample Type: Soil

Project: Dawson Area

Submitted by: All Terrane Mineral Expl.

ET #.	Tag #	Au (ppb)
1	S8R281103	10
2	S8R281104	25
3	S8R281105	5
4	S8R281106	10
5	S8R281107	10
6	S8R281108	5
7	S8R281109	5
8	S8R281110	10
9	S8R281111	5
10	S8R281112	10
11	S8R281113	5
12	S8R281114	10
13	S8R281115	10
14	S8R281116	20
15	S8R281117	10
16	S8R281118	10
17	S8R281119	5
18	S8R281120	5
19	S8R281121	5
20	S8R281122	20
21	S8R281123	10
22	S8R281124	20
23	S8R281125	20
24	S8R281126	10
25	S8R281127	10
26	S8R281128	<5
27	S8R281129	5
28	S8R281130	20
29	S8R281131	5
30	S8R281132	15
31	S8R281133	<5



Kestrel Gold Corp. AW11-8166

21-Sep-11

ET #.	Tag #	Au (ppb)
32	S8R281134	5
33	S8R281135	5
34	S8R281136	10
35	S8R281137	5
36	S8R281138	5
37	S8R281139	<5
38	S8R281140	5
39	S8R281141	<5
40	S8R281142	<5
41	S8R281143	5
42	S8R281144	5
43	S8R281145	5
44	S8R281146	<5
45	S8R281147	<5
46	S8R281148	10
47	S8R281149	230
48	S8R281150	<5
49	S8R281451	5
50	S8R281452	<5
51	S8R281453	10
52	S8R281454	<5
53	S8R281455	5
54	S8R281456	10
55	S8R281457	<5
56	S8R281458	5
57	S8R281459	5
58	S8R281460	5
59	S8R281461	<5
60	S8R281462	15
61	S8R281463	5
62	S8R281464	15
63	S8R281465	<5
64	S8R281466	<5
65	S8R281467	15
66	S8R281468	10
67	S8R281469	10
68	S8R281470	<5
69	S8R281471	<5
70	S8R281472	5
71	S8R281473	5
72	S8R281474	<5
73	S8R281475	5
74	S8R281476	10
75	S8R281477	<5

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8166

21-Sep-11

ET #.	Tag #	Au (ppb)
76	S8R281478	10
77	S8R281479	5
78	S8R281480	5
79	S8R281481	<5
80	S8R281482	<5
81	S8R281483	5
82	S8R281484	10
83	S8R281485	5
84	S8R281486	5
85	S8R281487	10
86	S8R281488	<5
87	S8R281489	5
88	S8R281490	<5
89	S8R281491	<5
90	S8R281492	5

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8166

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8166

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8166

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

QC DATA:

Repeat:

1	S8R281103	10
2	S8R281104	40
10	S8R281112	10
19	S8R281121	5
28	S8R281130	20
36	S8R281138	<5
45	S8R281147	<5
54	S8R281456	5
68	S8R281470	<5
71	S8R281473	10
80	S8R281482	<5
89	S8R281491	<5

PDFfill PDF Editor with Free Writer and Tools

Standard:

OXE86	610
OXE86	620
OXE86	595
OXE86	600
OXE86	620
OXE86	610
OXE86	620

FA Geochem/AA Finish

NM/sa
XLS/11


ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

Stewart Group
ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8166

Kestrel Gold Corp.
 #8-46225 Ranchero Drive
Chilliwack, BC
 V4Z 0A5
 Attn: Kevin Nephin

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 212
 Sample Type: Soil
Project: Dawson Area
 Submitted by: All Terrane Mineral Expl.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S8R281103	<0.2	1.75	10	148	<1	<5	0.19	<1	13	24	28	2.81	<5	0.04	12	12	0.96	435	2	0.03	16	590	18	<0.01	<5	3	<10	<5	14	0.07	<5	64	<5	4	70
2	S8R281104	<0.2	2.44	5	86	<1	5	0.14	<1	19	30	50	4.05	<5	0.02	6	16	1.86	820	1	0.03	25	340	18	<0.01	<5	6	<10	<5	10	0.06	<5	72	<5	4	98
3	S8R281105	<0.2	1.94	10	138	<1	<5	0.14	<1	14	38	40	3.16	<5	0.04	14	14	1.05	560	2	0.03	18	430	18	<0.01	<5	6	<10	<5	14	0.07	<5	70	<5	6	102
4	S8R281106	<0.2	2.30	<5	78	<1	5	0.13	<1	18	18	54	4.02	<5	0.02	6	14	1.71	845	1	0.03	16	360	15	<0.01	<5	5	<10	<5	10	0.03	<5	70	<5	4	90
5	S8R281107	<0.2	1.70	10	128	<1	<5	0.15	<1	12	24	26	2.67	<5	0.04	10	12	0.88	450	1	0.03	14	540	15	<0.01	<5	4	<10	<5	12	0.07	<5	64	<5	4	60
6	S8R281108	<0.2	2.27	5	76	<1	5	0.16	<1	18	18	56	3.84	<5	0.02	4	14	1.54	965	1	0.03	19	460	15	<0.01	<5	4	<10	<5	8	0.06	<5	64	<5	4	126
7	S8R281109	<0.2	1.92	10	98	<1	<5	0.13	<1	14	24	28	3.02	<5	0.03	8	14	1.06	440	1	0.03	16	310	15	<0.01	<5	4	<10	<5	10	0.08	<5	66	<5	4	66
8	S8R281110	<0.2	2.26	5	118	<1	5	0.19	<1	17	18	48	3.55	<5	0.02	8	16	1.49	760	1	0.03	17	530	15	<0.01	<5	5	<10	<5	10	0.04	<5	70	<5	6	76
9	S8R281111	0.2	1.94	5	190	<1	<5	0.51	<1	12	22	32	2.74	<5	0.03	10	14	1.05	620	1	0.03	16	450	12	0.01	<5	4	<10	<5	16	0.04	<5	66	<5	5	76
10	S8R281112	<0.2	2.25	<5	108	<1	5	0.27	<1	16	20	64	3.94	<5	0.02	6	14	1.67	830	1	0.03	17	670	15	<0.01	<5	6	<10	<5	10	0.02	<5	66	<5	7	96
11	S8R281113	<0.2	1.67	5	174	<1	<5	0.42	<1	13	32	24	2.41	<5	0.03	10	14	0.94	485	1	0.03	21	470	15	0.02	<5	4	<10	<5	18	0.04	<5	54	<5	4	78
12	S8R281114	<0.2	1.98	10	200	<1	<5	0.51	<1	19	36	38	3.19	<5	0.03	10	14	1.16	1280	2	0.04	25	630	18	0.03	<5	6	<10	<5	18	0.04	<5	64	<5	7	92
13	S8R281115	<0.2	2.83	<5	76	<1	5	0.36	<1	24	32	58	4.51	<5	0.01	4	16	2.53	1295	1	0.04	26	640	15	<0.01	<5	9	<10	<5	10	0.05	<5	84	<5	9	86
14	S8R281116	<0.2	1.74	5	70	<1	5	0.51	<1	18	24	54	4.07	<5	0.02	8	10	1.04	1090	1	0.03	21	880	21	<0.01	<5	11	<10	<5	6	<0.01	<5	64	<5	9	112
15	S8R281117	<0.2	2.23	5	84	<1	5	0.14	<1	16	22	56	3.59	<5	0.02	6	16	1.49	655	1	0.03	17	300	15	<0.01	<5	6	<10	<5	8	0.04	<5	74	<5	5	78
16	S8R281118	<0.2	1.94	5	204	<1	<5	0.32	<1	14	26	40	2.96	<5	0.03	10	14	1.09	630	1	0.03	19	610	15	0.01	<5	3	<10	<5	16	0.03	<5	64	<5	6	72
17	S8R281119	<0.2	1.75	5	202	<1	<5	0.20	<1	12	28	34	2.65	<5	0.04	12	14	0.93	425	1	0.03	19	440	15	<0.01	<5	5	<10	<5	16	0.07	<5	60	<5	6	64
18	S8R281120	<0.2	2.25	5	142	<1	5	0.20	<1	18	26	58	3.60	<5	0.02	8	16	1.62	705	1	0.03	20	460	15	<0.01	<5	6	<10	<5	12	0.04	<5	74	<5	5	86
19	S8R281121	<0.2	1.77	10	116	<1	<5	0.17	<1	14	24	26	2.37	<5	0.03	10	12	0.82	440	1	0.03	17	490	12	<0.01	<5	3	<10	<5	14	0.08	<5	58	<5	4	54
20	S8R281122	<0.2	1.78	10	200	<1	<5	0.15	<1	14	28	30	2.54	<5	0.04	12	14	0.73	450	1	0.03	19	370	15	<0.01	<5	3	<10	<5	14	0.06	<5	60	<5	5	58
21	S8R281123	<0.2	2.12	10	142	<1	5	0.18	<1	18	26	58	3.47	<5	0.03	10	14	1.40	750	2	0.03	23	550	15	<0.01	<5	6	<10	<5	12	0.06	<5	66	<5	7	80
22	S8R281124	<0.2	2.20	10	122	<1	5	0.16	<1	17	32	36	3.27	<5	0.04	10	14	1.27	545	2	0.03	22	460	15	<0.01	<5	4	<10	<5	12	0.10	<5	76	<5	3	64
23	S8R281125	<0.2	2.63	10	102	<1	10	0.19	<1	33	52	78	4.56	<5	0.01	4	16	2.41	985	2	0.03	37	490	18	<0.01	<5	8	<10	<5	8	0.06	<5	82	<5	8	72
24	S8R281126	<0.2	2.85	5	108	<1	10	0.14	<1	43	74	114	5.10	<5	0.01	6	16	2.84	1405	1	0.04	51	500	15	<0.01	<5	13	<10	<5	8	0.03	<5	100	<5	16	82
25	S8R281127	<0.2	1.79	10	148	<1	<5	0.16	<1	15	30	58	2.78	<5	0.05	14	14	0.90	540	2	0.03	21	320	15	<0.01	<5	5	<10	<5	14	0.10	<5	62	<5	10	70
26	S8R281128	<0.2	1.98	10	102	<1	<5	0.12	<1	14	28	32	3.00	<5	0.04	8	16	0.95	445	2	0.03	17	350	24	<0.01	<5	3	<10	<5	12	0.09	<5	68	<5	3	64
27	S8R281129	<0.2	2.10	10	218	<1	<5	0.14	<1	13	36	20	2.68	<5	0.05	16	16	0.49	245	2	0.03	16	290	21	<0.01	<5	5	<10	<5	16	0.10	<5	68	<5	5	54
28	S8R281130	<0.2	2.14	5	70	<1	<5	0.25	<1	19	10	52	3.11	<5	0.03	4	10	1.48	555	1	0.03	11	220	12	<0.01	<5	3	<10	<5	12	0.16	<5	54	<5	3	66
29	S8R281131	<0.2	1.83	5	170	<1	<5	0.13	<1	12	12	42	2.63	<5	0.05	8	8	0.96	540	1	0.03	9	380	18	<0.01	<5	2	<10	<5	10	0.07	<5	46	<5	5	68
30	S8R281132	<0.2	2.47	5	80	<1	5	0.12	<1	23	28	84	4.21	<5	0.02	6	14	1.81	1090	1	0.03	24	360	15	<0.01	<5	7	<10	<5	6	0.06	<5	66	<5	9	122
31	S8R281133	<0.2	1.84	10	82	<1	5	0.13	<1	13	24	34	2.92	<5	0.03	8	14	0.95	555	1	0.03	15	370	15	<0.01	<5	4	<10	<5	8	0.09	<5	56	<5	4	80
32	S8R281134	<0.2	2.40	5	80	<1	5	0.16	<1	20	42	96	4.08	<5	0.02	6	16	1.65	810	1	0.03	24	420	24	<0.01	<5	6	<10	<5	8	0.10	<5	82	<5	10	130
33	S8R281135	<0.2	2.26	5	80	<1	5	0.19	<1	19	32	60	3.58	<5	0.02	4	16	1.45	890	1	0.03	21	700	45	<0.01	<5	4	<10	<5	8	0.07	<5	66	<5	5	212
34	S8R281136	<0.2	2.35	<5	72	<1	5	0.33	<1	23	18	96	3.83	<5	0.01	4	14	1.49	955	1	0.03	15	600	21	<0.01	<5	6	<10	<5	12	0.06	<5	84	<5	8	104
35	S8R281137	<0.2	1.93	<5	134	<1	5	0.98	<1	20	18	78	3.23	<5	0.01	4	12	1.30	1695	2	0.03	16	710	18	0.05	<5	6	<10	<5	26	0.03	<5	64	<5	9	76

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
36	S8R281138	<0.2	1.51	5	146	<1	<5	0.13	<1	12	14	20	2.55	<5	0.33	6	10	0.72	430	1	0.02	10	360	12	<0.01	<5	3	<10	<5	8	0.12	<5	52	<5	4	60
37	S8R281139	<0.2	0.92	<5	84	<1	<5	0.08	<1	4	4	12	1.73	<5	0.18	20	4	0.51	445	<1	0.02	3	350	12	<0.01	<5	3	<10	<5	6	0.04	<5	10	<5	14	62
38	S8R281140	<0.2	1.62	5	116	<1	<5	0.17	<1	12	12	18	2.84	<5	0.20	6	10	0.90	465	1	0.02	8	450	12	<0.01	<5	3	<10	<5	10	0.11	<5	56	<5	5	62
39	S8R281141	<0.2	1.75	5	222	<1	<5	0.20	<1	16	16	36	3.07	<5	0.32	6	12	1.27	690	1	0.03	13	420	12	<0.01	<5	3	<10	<5	12	0.13	<5	64	<5	4	68
40	S8R281142	<0.2	1.53	<5	70	<1	<5	0.24	<1	16	16	32	2.33	<5	0.20	2	8	1.10	460	<1	0.02	14	520	9	<0.01	<5	2	<10	<5	10	0.10	<5	42	<5	2	50
41	S8R281143	<0.2	1.55	<5	196	<1	<5	0.23	<1	11	20	42	2.32	<5	0.04	6	8	0.80	265	1	0.03	15	410	12	0.02	<5	2	<10	<5	12	0.06	<5	50	<5	4	44
42	S8R281144	<0.2	1.74	5	98	<1	<5	0.21	<1	13	18	30	2.42	<5	0.03	6	10	0.87	340	1	0.02	14	450	12	<0.01	<5	2	<10	<5	12	0.07	<5	44	<5	3	50
43	S8R281145	<0.2	1.90	5	102	<1	<5	0.21	<1	14	16	28	2.65	<5	0.03	8	10	1.01	365	1	0.02	14	470	12	<0.01	<5	2	<10	<5	10	0.08	<5	44	<5	3	56
44	S8R281146	<0.2	1.88	<5	102	<1	<5	0.23	<1	16	16	36	2.81	<5	0.03	6	10	1.08	435	1	0.03	15	440	12	<0.01	<5	2	<10	<5	10	0.09	<5	46	<5	3	58
45	S8R281147	<0.2	1.91	<5	82	<1	<5	0.27	<1	17	16	36	2.97	<5	0.03	4	10	1.29	480	1	0.03	15	450	12	<0.01	<5	2	<10	<5	10	0.11	<5	46	<5	2	56
46	S8R281148	<0.2	1.80	<5	82	<1	<5	0.27	<1	17	18	44	2.90	<5	0.03	4	10	1.26	495	1	0.03	17	510	12	<0.01	<5	2	<10	<5	10	0.08	<5	46	<5	3	56
47	S8R281149	<0.2	0.20	460	1872	<1	5	1.00	<1	3	22	66	3.83	<5	0.07	2	2	0.02	105	17	0.03	17	50	21	0.13	30	<1	<10	<5	26	0.01	<5	10	<5	2	18
48	S8R281150	<0.2	0.27	<5	60	<1	<5	>10	<1	2	4	4	0.42	<5	0.11	<2	6	>10	210	<1	0.03	4	550	<3	0.09	<5	<1	<10	<5	44	<0.01	<5	4	<5	1	18
49	S8R281451	<0.2	2.00	<5	58	<1	5	0.27	<1	18	18	38	3.17	<5	0.03	2	10	1.55	530	1	0.03	17	480	9	<0.01	<5	2	<10	<5	10	0.09	<5	48	<5	2	56
50	S8R281452	<0.2	1.93	<5	38	<1	<5	0.30	<1	20	20	36	2.87	<5	0.01	<2	8	1.61	540	<1	0.02	19	500	9	<0.01	<5	2	<10	<5	10	0.11	<5	40	<5	2	48
51	S8R281453	<0.2	2.14	<5	62	<1	5	0.29	<1	20	22	40	3.16	<5	0.02	4	10	1.63	610	1	0.02	21	530	12	<0.01	<5	3	<10	<5	10	0.09	<5	52	<5	3	54
52	S8R281454	<0.2	2.46	<5	76	<1	5	0.31	<1	22	24	62	3.48	<5	0.01	4	12	1.96	690	1	0.03	22	470	12	<0.01	<5	4	<10	<5	12	0.07	<5	68	<5	4	58
53	S8R281455	<0.2	2.72	<5	40	<1	5	0.31	<1	27	24	64	1.07	<5	<0.01	<2	14	2.29	1090	1	0.03	21	740	18	0.02	<5	5	<10	<5	6	0.12	<5	68	<5	5	56
54	S8R281456	0.4	2.63	5	34	<1	5	0.44	<1	29	18	90	4.09	<5	<0.01	<2	14	2.19	1165	1	0.03	20	760	18	0.04	<5	5	<10	<5	8	0.11	<5	64	<5	6	56
55	S8R281457	<0.2	1.99	<5	24	<1	<5	0.21	<1	17	4	28	3.02	<5	0.01	<2	10	1.71	640	<1	0.02	7	440	12	<0.01	<5	2	<10	<5	12	0.14	<5	44	<5	3	52
56	S8R281458	<0.2	1.98	10	64	<1	5	0.10	<1	13	38	40	3.49	<5	0.03	6	14	1.12	535	2	0.03	18	360	18	<0.01	<5	4	<10	<5	8	0.12	<5	70	<5	3	104
57	S8R281459	<0.2	2.09	10	158	<1	5	0.14	<1	16	38	68	3.13	<5	0.03	12	16	0.91	755	2	0.03	24	440	24	<0.01	<5	5	<10	<5	12	0.07	<5	58	<5	7	118
58	S8R281460	<0.2	2.07	10	146	<1	5	0.23	<1	14	22	62	3.05	<5	0.03	6	14	1.12	565	1	0.03	18	510	24	<0.01	<5	6	<10	<5	12	0.04	<5	62	<5	7	88
59	S8R281461	<0.2	2.36	5	64	<1	5	0.18	<1	20	14	46	3.78	<5	0.02	4	12	1.67	690	1	0.03	13	340	21	<0.01	<5	5	<10	<5	12	0.13	<5	74	<5	5	78
60	S8R281462	<0.2	1.93	5	96	<1	<5	0.13	<1	17	22	40	2.82	<5	0.03	6	12	0.97	560	1	0.03	18	370	15	<0.01	<5	3	<10	<5	10	0.05	<5	52	<5	4	74
61	S8R281463	<0.2	1.92	10	96	<1	5	0.08	<1	26	30	62	3.90	<5	0.03	8	16	1.01	905	2	0.03	24	410	21	<0.01	<5	4	<10	<5	8	0.04	<5	54	<5	4	78
62	S8R281464	<0.2	1.87	5	110	<1	5	0.15	<1	16	16	48	3.45	<5	0.03	8	14	0.93	795	2	0.03	15	420	18	0.01	<5	5	<10	<5	16	0.03	<5	52	<5	5	86
63	S8R281465	<0.2	2.39	<5	60	<1	10	0.12	<1	22	22	78	4.53	<5	<0.01	4	14	1.51	1335	1	0.03	14	270	15	<0.01	<5	10	<10	<5	8	<0.01	<5	106	<5	5	74
64	S8R281466	<0.2	1.96	5	38	<1	5	0.09	<1	20	184	50	3.49	<5	0.01	4	10	1.64	1055	1	0.03	64	610	24	<0.01	<5	7	<10	<5	6	0.04	<5	76	<5	3	98
65	S8R281467	<0.2	2.41	10	60	<1	10	0.06	<1	42	58	138	4.63	<5	0.01	6	16	1.72	1595	2	0.03	34	310	51	<0.01	<5	9	<10	<5	4	0.01	<5	54	<5	6	186
66	S8R281468	<0.2	1.32	<5	198	<1	<5	0.26	<1	9	10	16	2.26	<5	0.24	4	6	0.66	425	2	0.02	15	460	9	<0.01	<5	2	<10	<5	10	0.12	<5	46	<5	4	52
67	S8R281469	<0.2	1.39	<5	80	<1	<5	0.41	<1	15	14	28	2.19	<5	0.03	4	6	0.83	455	<1	0.02	11	440	9	0.02	<5	3	<10	<5	14	0.07	<5	46	<5	3	48
68	S8R281470	<0.2	1.83	<5	178	<1	<5	0.46	<1	15	12	32	2.86	<5	0.38	4	10	1.31	735	<1	0.03	9	930	9	<0.01	<5	3	<10	<5	16	0.13	<5	56	<5	5	70
69	S8R281471	<0.2	1.88	<5	108	<1	<5	0.39	<1	18	32	42	2.87	<5	0.09	4	10	1.34	625	1	0.03	21	680	9	<0.01	<5	3	<10	<5	14	0.09	<5	58	<5	3	56
70	S8R281472	<0.2	1.75	5	160	<1	5	0.45	<1	16	16	46	2.98	<5	0.04	6	12	1.14	445	1	0.03	14	540	12	0.03	<5	4	<10	<5	18	0.05	<5	62	<5	5	64
71	S8R281473	<0.2	1.81	<5	132	<1	<5	0.57	<1	16	12	32	2.71	<5	0.04	4	8	1.19	775	1	0.03	12	670	9	0.02	<5	3	<10	<5	18	0.05	<5	50	<5	3	66
72	S8R281474	<0.2	1.77	<5	168	<1	5	0.36	<1	19	10	22	3.48	<5	0.03	4	8	1.32	755	1	0.03	10	430	12	0.02	<5	5	<10	<5	12	0.06	<5	72	<5	3	70
73	S8R281475	<0.2	2.11	<5	168	<1	5	0.33	<1	21	12	56	4.00	<5	0.14	4	10	1.65	690	1	0.03	11	660	15	<0.01	<5	4	<10	<5	12	0.10	<5	102	<5	3	84
74	S8R281476	<0.2	2.82	<5	206	<1	10	0.33	<1	31	6	62	5.46	<5	0.34	<2	12	2.26	1200	1	0.04	9	540	15	<0.01	<5	4	<10	<5	10	0.13	<5	148	<5	2	88
75	S8R281477	<0.2	2.77	<5	160	<1	5	0.30	<1	27	10	70	4.92	<5	0.29	4	14	2.30	935	1	0.03	12	650	15	<0.01	<5	4	<10	<5	12	0.16	<5	110	<5	3	82
76	S8R281478	<0.2	2.19	<5	88	<1																														

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
81	S8R281483	<0.2	2.10	5	118	<1	5	0.16	<1	27	16	78	4.00	<5	0.02	6	12	1.39	925	1	0.03	24	410	18	<0.01	<5	6	<10	<5	12	0.03	<5	68	<5	4	116
82	S8R281484	<0.2	2.11	10	196	<1	<5	0.13	<1	15	42	38	2.89	<5	0.04	10	14	0.92	815	2	0.03	24	340	21	<0.01	<5	5	<10	<5	10	0.05	<5	62	<5	5	106
83	S8R281485	<0.2	1.67	5	154	<1	5	0.28	<1	20	22	34	2.84	<5	0.02	18	8	1.19	1000	1	0.03	17	910	27	<0.01	<5	5	<10	<5	12	0.01	<5	28	<5	12	122
84	S8R281486	<0.2	2.03	10	148	<1	5	0.14	<1	18	48	82	3.57	<5	0.02	8	14	1.53	965	1	0.03	35	300	21	<0.01	<5	5	<10	<5	10	0.04	<5	54	<5	9	120
85	S8R281487	<0.2	1.93	10	150	<1	5	0.20	<1	17	52	52	2.90	<5	0.03	8	12	1.23	635	1	0.03	31	320	18	<0.01	<5	5	<10	<5	10	0.08	<5	58	<5	5	126
86	S8R281488	<0.2	2.08	5	50	<1	<5	0.22	<1	17	52	76	3.04	<5	0.02	2	10	1.88	875	<1	0.02	27	460	15	<0.01	<5	5	<10	<5	8	0.11	<5	46	<5	6	146
87	S8R281489	<0.2	1.77	5	58	<1	5	0.15	<1	11	14	22	3.24	<5	0.02	6	10	0.96	630	1	0.03	10	640	12	<0.01	<5	4	<10	<5	8	0.03	<5	40	<5	4	90
88	S8R281490	<0.2	1.92	<5	96	<1	5	0.12	<1	17	8	68	4.06	<5	0.02	8	8	1.13	1015	<1	0.03	11	560	21	<0.01	<5	11	<10	<5	4	0.01	<5	60	<5	11	138
89	S8R281491	<0.2	2.14	5	104	<1	<5	0.17	<1	14	16	40	3.23	<5	0.03	8	12	1.20	775	2	0.03	13	460	15	<0.01	<5	4	<10	<5	10	0.09	<5	50	<5	6	72
90	S8R281492	<0.2	2.55	<5	24	<1	5	0.27	<1	26	14	34	3.91	<5	<0.01	<2	10	2.09	995	1	0.03	15	470	12	<0.01	<5	2	<10	<5	12	0.13	<5	64	<5	2	72

PDFill PDF Editor with Free Writer and Tools

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

QC DATA:																																				
Repeat:																																				
1	S8R281103	<0.2	1.69	10	146	<1	<5	0.18	<1	13	24	28	2.73	<5	0.03	12	12	0.95	430	1	0.03	16	580	18	<0.01	<5	3	<10	<5	14	0.07	<5	62	<5	4	66
10	S8R281112	<0.2	2.31	<5	112	<1	5	0.26	<1	16	22	68	3.90	<5	0.02	6	16	1.70	855	1	0.03	17	590	15	<0.01	<5	7	<10	<5	10	0.02	<5	68	<5	7	98
19	S8R281121	<0.2	1.75	10	116	<1	<5	0.17	<1	13	24	26	2.30	<5	0.03	10	12	0.78	435	1	0.03	16	490	12	<0.01	<5	3	<10	<5	12	0.08	<5	56	<5	4	52
36	S8R281138	<0.2	1.51	5	144	<1	<5	0.13	<1	12	14	20	2.54	<5	0.33	6	10	0.70	435	1	0.02	10	360	12	<0.01	<5	3	<10	<5	8	0.12	<5	52	<5	4	58

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
45	S8R281147	<0.2	1.93	<5	80	<1	<5	0.27	<1	17	16	36	2.84	<5	0.03	4	10	1.26	470	<1	0.02	14	460	12	<0.01	<5	2	<10	<5	10	0.11	<5	46	<5	2	52
54	S8R281456	0.4	2.61	5	32	<1	5	0.43	<1	29	18	90	4.08	<5	<0.01	<2	14	2.15	1185	1	0.03	20	770	18	0.05	<5	5	<10	<5	8	0.11	<5	62	<5	6	56
71	S8R281473	<0.2	1.86	5	140	<1	<5	0.59	<1	17	14	34	2.79	<5	0.04	4	8	1.22	790	<1	0.03	13	640	9	0.02	<5	3	<10	<5	18	0.05	<5	52	<5	3	70
80	S8R281482	<0.2	2.32	<5	68	<1	5	0.18	<1	19	14	42	3.75	<5	0.03	2	10	1.45	660	1	0.03	10	240	12	<0.01	<5	2	<10	<5	8	0.13	<5	62	<5	2	66
89	S8R281491	<0.2	2.09	5	102	<1	<5	0.17	<1	14	16	38	3.20	<5	0.03	8	12	1.13	760	1	0.03	13	470	15	<0.01	<5	4	<10	<5	8	0.08	<5	48	<5	6	70

Standard:

Pb129a	11.8	0.83	5	64	<1	<5	0.47	58	6	10	1454	1.59	<5	0.11	4	<2	0.65	370	2	0.04	5	410	6123	0.81	15	<1	<10	<5	30	0.06	<5	18	<5	3	9942
Pb129a	11.6	0.83	5	62	<1	<5	0.47	57	6	10	1472	1.56	<5	0.11	4	<2	0.65	370	2	0.04	5	420	6120	0.83	15	<1	<10	<5	32	0.06	<5	18	<5	3	9962
Pb129a	12.0	0.86	5	68	<1	<5	0.46	57	6	10	1446	1.53	<5	0.11	4	<2	0.68	370	2	0.04	5	400	6099	0.83	15	<1	<10	<5	30	0.06	<5	20	<5	3	9920
Till3	1.6	1.12	85	44	<1	<5	0.52	<1	13	64	22	2.10	<5	0.08	15	20	0.56	310	2	0.04	33	450	18	0.01	<5	3	<10	<5	14	0.07	<5	38	<5	7	40
Till3	1.4	1.04	80	40	<1	<5	0.58	<1	15	72	20	2.09	<5	0.10	16	22	0.58	315	2	0.06	36	430	18	0.01	<5	4	<10	<5	15	0.08	<5	40	<5	8	40
Till3	1.6	1.07	80	44	<1	<5	0.52	<1	13	64	22	2.10	<5	0.08	16	20	0.55	310	2	0.04	33	450	18	0.01	<5	3	<10	<5	14	0.07	<5	38	<5	7	38
Till3	1.4	1.09	85	38	<1	<5	0.55	<1	12	66	22	1.98	<5	0.08	14	16	0.55	305	2	0.04	32	460	21	<0.01	<5	3	<10	<5	14	0.09	<5	36	<5	6	38

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/sa

dt/2_8166AS, 1_8166BS

XLS/11


 ECO TECH LABORATORY LTD.
 Norman Monteith
 B.C. Certified Assayer



CERTIFICATE OF ANALYSIS AW 2011-8167

Kestrel Gold Corp.
#8-46225 Rancho Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

09-Sep-11

No. of samples received: 236

Sample Type: Soil

Project: Dawson Area

Submitted by: Darwin Wreggit

ET #.	Tag #	Au (ppb)
1	S8R279497	15
2	S8R279498	10
3	S8R279499	5
4	S8R279500	10
5	S8R279501	5
6	S8R279502	5
7	S8R279503	5
8	S8R279504	10
9	S8R279505	0
10	S8R279506	15
11	S8R279507	10
12	S8R279508	10
13	S8R279509	90
14	S8R279510	10
15	S8R279511	5
16	S8R279512	10
17	S8R279513	5
18	S8R279514	<5
19	S8R279515	15
20	S8R279516	5
21	S8R279517	5
22	S8R279518	5
23	S8R279519	5
24	S8R279520	<5
25	S8R279521	5
26	S8R279522	5
27	S8R279523	<5
28	S8R279524	10
29	S8R279525	5
30	S8R279526	10

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8167

09-Sep-11

ET #.	Tag #	Au (ppb)
31	S8R279527	15
32	S8R279528	<5
33	S8R279529	<5
34	S8R279530	5
35	S8R279531	10
36	S8R279532	15
37	S8R279533	10
38	S8R279534	15
39	S8R279535	10
40	S8R279536	15
41	S8R279537	<5
42	S8R279538	<5
43	S8R279539	5
44	S8R279540	<5
45	S8R279541	<5
46	S8R279542	5
47	S8R279543	5
48	S8R279544	10
49	S8R279545	<5
50	S8R279546	5
51	S8R279547	5
52	S8R279548	20
53	S8R279549	10
54	S8R279550	<5
55	S8R279551	10
56	S8R279552	5
57	S8R279553	15
58	S8R279554	25
59	S8R279555	10
60	S8R279556	15
61	S8R279557	10
62	S8R279558	15
63	S8R279559	25
64	S8R279560	5
65	S8R279561	15
66	S8R279562	10
67	S8R279563	5
68	S8R279564	<5
69	S8R279565	<5
70	S8R279566	5
71	S8R279567	<5
72	S8R279568	<5
73	S8R279569	<5
74	S8R279570	<5

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8167

09-Sep-11

ET #.	Tag #	Au (ppb)
75	S8R279571	5
76	S8R279572	5
77	S8R279573	5
78	S8R279574	<5
79	S8R279575	<5
80	S8R279576	5
81	S8R279577	5
82	S8R279578	<5
83	S8R279579	15
84	S8R279580	5
85	S8R279581	10
86	S8R279582	5
87	S8R279583	5

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8167

09-Sep-11

<u>ET #.</u>	<u>Tag #</u>	<u>Au</u> <u>(ppb)</u>

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8167

09-Sep-11

<u>ET #.</u>	<u>Tag #</u>	<u>Au</u> <u>(ppb)</u>
--------------	--------------	---------------------------

187	S8R288001	10
188	S8R288002	20
189	S8R288003	<5
190	S8R288004	<5
191	S8R288005	10
192	S8R288006	10
193	S8R288007	15
194	S8R288008	10
195	S8R288009	10
196	S8R288010	<5
197	S8R288011	<5
198	S8R288012	<5
199	S8R288013	<5
200	S8R288014	<5
201	S8R288015	5
202	S8R288016	5
203	S8R288017	20
204	S8R288018	<5
205	S8R288019	30
206	S8R288020	<5

PDFfill PDF Editor with Free Writer and Tools



Kestrel Gold Corp. AW11-8167

09-Sep-11

ET #.	Tag #	Au (ppb)
207	S8R288021	<5
208	S8R288022	<5
209	S8R288023	<5
210	S8R288024	5
211	S8R288025	<5
212	S8R288026	<5
213	S8R288027	<5
214	S8R288028	<5
215	S8R288029	5
216	S8R288030	5
217	S8R288031	10
218	S8R288032	<5
219	S8R288033	<5
220	S8R288034	<5
221	S8R288035	<5
222	S8R288036	10
223	S8R288037	5
224	S8R288038	<5
225	S8R288039	<5
226	S8R288040	<5
227	S8R288041	<5
228	S8R288042	<5
229	S8R288043	<5
230	S8R288044	10
231	S8R288045	<5
232	S8R288046	<5
233	S8R288047	<5
234	S8R288048	<5
235	S8R288049	<5
236	S8R288050	<5

QC DATA:

Repeat:

1	S8R279497	10
10	S8R279506	10
19	S8R279515	10
28	S8R279524	5
37	S8R279533	10
45	S8R279541	5
55	S8R279551	5
63	S8R279559	20
71	S8R279567	<5
80	S8R279576	5

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8167

9-Sep-11

ET #.	Tag #	Au (ppb)
1		
1		
1		
1		
1		
1		
1		
1		
1		
1		
194	S8R288008	10
204	S8R288018	5
211	S8R288025	<5
221	S8R288035	<5
229	S8R288043	<5

Standard:

OXE86	610
OXE86	615
OXE86	620
OXE86	605
OXE86	610
OXE86	620
OXE86	600

FA Geochem/AA Finish

NM/mb/el
 XLS/11

ECO TECH LABORATORY LTD.

Norman Monteith
 B.C. Certified Assayer

Stewart Group
ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8167

Kestrel Gold Corp.
 #8-46225 Ranchero Drive
Chilliwack, BC
 V4Z 0A5
 Attn: Kevin Nephin

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 236
 Sample Type: Soil
Project: Dawson Area
 Submitted by: Darwin Wreggit

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S8R279497	0.2	1.30	<5	72	<1	<5	0.30	<1	18	8	88	3.66	<5	0.06	8	8	0.99	800	<1	0.07	10	710	<3	0.06	<5	10	<10	<5	6	<0.01	<5	90	<5	10	56
2	S8R279498	<0.2	1.37	5	152	<1	<5	0.35	<1	18	16	48	2.85	<5	0.04	6	10	1.27	475	<1	0.08	24	420	<3	0.06	<5	6	<10	<5	12	0.03	<5	56	<5	7	56
3	S8R279499	<0.2	2.37	<5	188	<1	<5	0.27	<1	36	42	98	4.97	<5	0.10	2	14	2.42	975	<1	0.06	27	560	<3	0.06	<5	6	<10	<5	8	0.11	<5	132	<5	3	76
4	S8R279500	<0.2	1.44	<5	182	<1	<5	0.32	<1	17	12	38	3.29	<5	0.23	4	8	1.37	650	<1	0.08	10	670	<3	0.07	<5	4	<10	<5	8	0.07	<5	82	<5	3	60
5	S8R279501	<0.2	1.20	<5	134	<1	<5	0.23	<1	14	16	36	2.91	<5	0.15	4	8	1.09	530	<1	0.08	13	480	<3	0.05	<5	2	<10	<5	12	0.07	<5	44	<5	2	50
6	S8R279502	<0.2	1.29	<5	104	<1	<5	0.15	<1	11	16	24	2.62	<5	0.12	6	8	1.20	455	<1	0.08	11	400	<3	0.06	<5	3	<10	<5	8	0.05	<5	54	<5	3	58
7	S8R279503	<0.2	1.12	<5	116	<1	<5	0.18	<1	9	18	18	2.32	<5	0.10	6	8	0.80	325	<1	0.07	11	360	<3	0.06	<5	3	<10	<5	10	0.05	<5	54	<5	3	48
8	S8R279504	<0.2	1.14	<5	176	<1	<5	0.20	<1	11	10	16	2.64	<5	0.18	4	10	0.84	470	<1	0.07	8	570	<3	0.06	<5	3	<10	<5	8	0.07	<5	46	<5	3	56
9	S8R279505	<0.2	1.52	<5	160	<1	<5	0.33	<1	12	14	24	3.38	<5	0.19	10	12	1.46	660	<1	0.08	10	890	<3	0.08	<5	4	<10	<5	12	0.04	<5	52	<5	7	78
10	S8R279506	0.4	1.23	20	230	<1	<5	0.39	<1	13	26	26	2.60	<5	0.21	12	14	1.07	455	1	0.09	19	740	6	0.06	<5	4	<10	<5	18	0.05	<5	36	<5	6	76
11	S8R279507	<0.2	1.43	10	270	<1	<5	0.21	<1	13	12	22	3.53	<5	0.28	12	14	0.94	665	<1	0.09	10	650	6	0.06	<5	5	<10	<5	8	0.07	<5	52	<5	6	72
12	S8R279508	<0.2	1.27	<5	264	<1	<5	0.26	<1	14	24	40	2.98	<5	0.28	6	12	1.19	845	<1	0.08	19	790	<3	0.05	<5	4	<10	<5	8	0.06	<5	70	<5	4	74
13	S8R279509	0.4	0.58	200	196	<1	<5	0.23	<1	21	10	34	4.08	<5	0.26	22	4	0.41	985	2	0.06	27	1060	6	0.10	<5	5	<10	<5	12	0.02	<5	28	<5	10	38
14	S8R279510	<0.2	1.64	5	246	<1	<5	0.26	<1	31	36	126	3.56	<5	0.18	8	12	1.37	755	2	0.07	27	370	<3	0.09	<5	5	<10	<5	12	0.10	<5	96	<5	4	66
15	S8R279511	<0.2	1.48	5	160	<1	<5	0.15	<1	14	48	40	2.88	<5	0.15	8	12	0.94	380	<1	0.08	25	540	3	0.07	<5	4	<10	<5	10	0.06	<5	58	<5	4	54
16	S8R279512	<0.2	1.65	5	184	<1	<5	0.21	<1	18	14	62	3.70	<5	0.21	6	12	1.26	610	<1	0.07	15	650	<3	0.08	<5	4	<10	<5	8	0.06	<5	78	<5	4	72
17	S8R279513	<0.2	1.98	<5	76	<1	<5	0.15	<1	19	38	52	4.12	<5	0.16	6	10	1.80	1235	<1	0.08	25	470	<3	0.06	<5	14	<10	<5	4	<0.01	<5	98	<5	11	58
18	S8R279514	<0.2	1.73	5	96	<1	<5	0.13	<1	14	14	36	3.01	<5	0.10	4	10	1.06	365	<1	0.08	11	240	<3	0.05	<5	2	<10	<5	6	0.14	<5	58	<5	2	50
19	S8R279515	<0.2	2.48	<5	68	<1	<5	0.08	<1	21	4	58	5.32	<5	0.08	2	12	1.81	1105	<1	0.08	6	220	<3	0.04	<5	7	<10	<5	4	0.02	<5	128	<5	4	76
20	S8R279516	<0.2	2.17	<5	34	<1	<5	0.10	<1	24	10	84	4.76	<5	0.10	<2	14	1.55	865	<1	0.09	13	330	<3	0.06	<5	5	<10	<5	2	0.06	<5	62	<5	2	82
21	S8R279517	<0.2	1.93	<5	116	<1	<5	0.20	<1	24	222	66	3.37	<5	0.10	8	10	2.21	990	<1	0.09	83	360	<3	0.05	<5	9	<10	<5	12	0.07	<5	48	<5	6	66
22	S8R279518	<0.2	2.30	<5	142	<1	<5	0.25	<1	22	126	72	4.09	<5	0.06	4	12	2.46	775	<1	0.08	60	370	<3	0.05	<5	8	<10	<5	8	0.05	<5	92	<5	4	74
23	S8R279519	<0.2	3.33	<5	84	<1	<5	0.16	<1	35	330	80	5.52	<5	0.04	4	16	4.24	1060	<1	0.08	114	240	<3	0.05	<5	15	<10	<5	6	0.10	<5	170	<5	4	80
24	S8R279520	<0.2	2.65	<5	86	<1	<5	0.15	<1	27	102	92	4.74	<5	0.03	<2	12	2.86	965	<1	0.08	51	300	<3	0.05	<5	6	<10	<5	6	0.09	<5	126	<5	2	126
25	S8R279521	<0.2	2.04	<5	88	<1	<5	0.13	<1	20	66	62	3.68	<5	0.02	6	12	2.00	600	<1	0.08	39	210	3	0.06	<5	5	<10	<5	8	0.09	<5	76	<5	3	72
26	S8R279522	<0.2	2.40	<5	70	<1	<5	0.12	<1	23	252	70	3.79	<5	<0.01	4	14	2.77	515	<1	0.07	91	150	<3	0.04	<5	7	<10	<5	4	0.10	<5	92	<5	4	70
27	S8R279523	1.6	2.28	<5	88	<1	<5	0.11	<1	22	48	76	4.53	<5	<0.01	2	12	1.81	705	<1	0.08	28	320	3	0.05	<5	7	<10	<5	4	0.05	<5	94	<5	3	86
28	S8R279524	<0.2	1.95	<5	130	<1	<5	0.18	<1	20	108	50	3.65	<5	0.02	6	12	1.99	650	<1	0.09	49	370	<3	0.05	<5	6	<10	<5	10	0.07	<5	82	<5	3	66
29	S8R279525	<0.2	1.57	<5	122	<1	<5	0.15	<1	15	118	30	2.81	<5	<0.01	6	12	1.46	400	<1	0.07	47	310	<3	0.04	<5	4	<10	<5	8	0.06	<5	62	<5	2	50
30	S8R279526	<0.2	1.51	<5	106	<1	<5	0.15	<1	17	136	36	2.55	<5	<0.01	6	12	1.64	435	<1	0.09	53	290	<3	0.03	<5	4	<10	<5	8	0.06	<5	56	<5	3	46

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
31	S8R279527	<0.2	2.39	<5	178	<1	<5	0.33	<1	26	184	84	4.39	<5	<0.01	8	16	2.77	850	<1	0.07	73	450	3	0.04	<5	12	<10	<5	14	0.06	<5	100	<5	8	66
32	S8R279528	<0.2	2.00	<5	80	<1	<5	0.16	<1	21	244	62	3.09	<5	<0.01	6	12	2.47	640	<1	0.08	87	290	<3	0.02	<5	6	<10	<5	6	0.07	<5	64	<5	6	52
33	S8R279529	<0.2	1.82	<5	116	<1	<5	0.18	<1	17	152	50	2.87	<5	0.02	8	10	2.10	625	<1	0.09	55	370	<3	0.03	<5	7	<10	<5	8	0.07	<5	58	<5	5	58
34	S8R279530	<0.2	1.21	<5	20	<1	<5	0.12	<1	17	258	34	1.65	<5	<0.01	<2	8	1.74	275	<1	0.08	89	200	<3	0.02	<5	2	<10	<5	4	0.05	<5	28	<5	2	22
35	S8R279531	<0.2	0.98	<5	140	<1	<5	0.18	<1	7	14	10	1.94	<5	0.02	6	8	0.69	255	<1	0.09	9	470	<3	0.06	<5	2	<10	<5	10	0.04	<5	38	<5	4	48
36	S8R279532	0.2	0.90	<5	102	<1	<5	0.17	<1	7	12	12	1.89	<5	0.10	6	6	0.63	220	<1	0.08	9	550	<3	0.05	<5	2	<10	<5	8	0.04	<5	36	<5	2	46
37	S8R279533	<0.2	0.81	<5	80	<1	<5	0.16	<1	7	10	14	1.64	<5	0.08	4	6	0.63	210	<1	0.08	8	530	<3	0.04	<5	1	<10	<5	8	0.03	<5	32	<5	2	38
38	S8R279534	<0.2	0.92	<5	64	<1	<5	0.19	<1	14	12	14	1.99	<5	0.08	4	6	0.83	510	<1	0.08	10	580	<3	0.04	<5	2	<10	<5	8	0.03	<5	38	<5	1	42
39	S8R279535	<0.2	1.03	<5	90	<1	<5	0.24	<1	12	14	18	2.19	<5	0.05	4	6	0.92	525	<1	0.07	12	540	<3	0.05	<5	2	<10	<5	8	0.03	<5	44	<5	2	46
40	S8R279536	<0.2	1.33	<5	136	<1	<5	0.40	<1	15	20	30	2.58	<5	0.05	4	8	1.17	390	<1	0.08	16	470	<3	0.05	<5	3	<10	<5	12	0.04	<5	58	<5	2	60
41	S8R279537	<0.2	1.04	<5	112	<1	<5	0.34	<1	12	14	18	2.13	<5	0.02	4	6	0.82	460	<1	0.07	13	460	<3	0.05	<5	3	<10	<5	12	0.02	<5	42	<5	2	48
42	S8R279538	<0.2	1.32	<5	144	<1	<5	0.30	<1	17	20	34	2.91	<5	0.02	4	8	1.04	520	<1	0.08	18	560	<3	0.04	<5	4	<10	<5	8	0.02	<5	46	<5	4	64
43	S8R279539	0.2	1.23	<5	114	<1	<5	0.68	<1	17	16	54	3.35	<5	0.03	6	6	1.01	740	<1	0.08	15	660	3	0.07	<5	7	<10	<5	14	0.01	<5	60	<5	8	72
44	S8R279540	<0.2	1.44	10	80	<1	<5	0.35	<1	14	18	32	2.75	<5	<0.01	2	8	1.33	665	<1	0.08	16	620	<3	0.05	<5	3	<10	<5	10	0.02	<5	44	<5	2	52
45	S8R279541	0.2	1.61	<5	72	<1	<5	0.23	<1	16	34	34	3.01	<5	<0.01	2	8	1.64	760	<1	0.08	23	740	3	0.03	<5	3	<10	<5	6	0.03	<5	56	<5	2	72
46	S8R279542	<0.2	1.67	<5	60	<1	<5	0.20	<1	18	14	40	3.33	<5	0.02	2	8	1.56	575	<1	0.07	14	500	<3	0.05	<5	2	<10	<5	6	0.05	<5	52	<5	1	58
47	S8R279543	<0.2	1.42	<5	52	<1	<5	0.17	<1	14	18	18	2.56	<5	<0.01	2	8	1.28	415	<1	0.07	16	390	<3	0.04	<5	1	<10	<5	6	0.04	<5	36	<5	1	44
48	S8R279544	<0.2	1.34	<5	32	<1	<5	0.25	<1	16	18	40	3.38	<5	<0.01	<2	6	1.57	500	<1	0.08	18	590	<3	0.03	<5	1	<10	<5	6	0.05	<5	32	<5	<1	36
49	S8R279545	<0.2	1.25	<5	24	<1	<5	0.29	<1	9	<2	18	2.55	<5	<0.01	<2	6	1.24	535	<1	0.09	3	1080	<3	0.03	<5	<1	<10	<5	6	0.04	<5	20	<5	1	56
50	S8R279546	<0.2	1.47	5	40	<1	<5	0.28	<1	17	10	54	2.90	<5	<0.01	2	6	1.51	650	<1	0.06	10	780	<3	0.04	<5	2	<10	<5	8	0.05	<5	42	<5	2	50
51	S8R279547	<0.2	1.11	5	116	<1	<5	0.20	<1	8	16	26	2.36	<5	<0.01	8	10	0.60	255	<1	0.08	15	520	3	0.03	<5	1	<10	<5	12	0.03	<5	40	<5	4	44
52	S8R279548	<0.2	1.26	<5	78	<1	<5	0.19	<1	12	8	26	2.58	<5	<0.01	8	8	0.89	490	<1	0.08	9	660	<3	0.04	<5	2	<10	<5	8	0.02	<5	32	<5	3	50
53	S8R279549	<0.2	1.03	40	106	<1	<5	1.32	<1	7	26	48	3.01	<5	0.10	6	8	0.58	405	10	0.14	33	690	<3	0.14	<5	4	<10	<5	36	0.10	<5	46	<5	8	54
54	S8R279550	<0.2	0.08	<5	26	<1	<5	>10	<1	1	<2	<2	0.67	<5	0.08	<2	<2	1.10	230	<1	0.05	4	230	<3	0.02	<5	<1	<10	<5	52	<0.01	<5	4	<5	1	14
55	S8R279551	<0.2	1.19	5	224	<1	<5	0.33	<1	10	18	26	2.33	<5	0.02	10	10	0.98	515	<1	0.08	14	600	6	0.11	<5	3	<10	<5	14	0.02	<5	36	<5	6	50
56	S8R279552	0.2	1.24	5	210	<1	<5	0.50	<1	10	22	26	2.42	<5	<0.01	8	8	0.65	455	<1	0.09	16	660	6	0.12	<5	3	<10	<5	18	0.03	<5	38	<5	5	52
57	S8R279553	0.4	1.45	5	122	<1	<5	0.47	<1	20	54	76	2.76	<5	<0.01	8	10	1.02	755	<1	0.09	29	480	9	0.09	<5	6	<10	<5	12	0.02	<5	52	<5	11	58
58	S8R279554	0.2	1.56	5	134	<1	<5	0.21	3	32	78	82	3.58	<5	<0.01	4	10	1.56	2180	<1	0.08	43	430	42	0.08	<5	10	<10	<5	4	<0.01	<5	52	<5	9	170
59	S8R279555	0.4	1.36	5	150	<1	<5	0.39	<1	19	32	82	3.29	<5	<0.01	8	10	0.94	1085	<1	0.09	24	560	9	0.08	<5	5	<10	<5	10	0.02	<5	44	<5	9	90
60	S8R279556	0.4	1.47	10	114	<1	<5	0.23	<1	21	30	86	3.74	<5	<0.01	8	12	0.98	800	1	0.08	24	470	18	0.05	<5	6	<10	<5	6	0.02	<5	42	<5	8	104
61	S8R279557	0.2	1.42	<5	88	<1	<5	0.16	<1	21	16	70	3.33	<5	<0.01	6	10	0.95	700	<1	0.08	15	500	3	0.05	<5	5	<10	<5	8	0.02	<5	42	<5	5	64
62	S8R279558	0.2	1.41	5	118	<1	<5	0.15	<1	16	36	44	3.14	<5	<0.01	8	12	1.00	445	<1	0.09	23	500	6	0.04	<5	5	<10	<5	10	0.03	<5	50	<5	4	78
63	S8R279559	0.6	1.77	10	126	<1	<5	0.24	<1	40	28	110	4.12	<5	<0.01	4	12	1.52	1325	<1	0.08	21	520	12	0.10	<5	8	<10	<5	8	0.02	<5	50	<5	5	90
64	S8R279560	0.2	1.19	<5	136	<1	<5	0.33	<1	15	30	70	2.54	<5	<0.01	4	8	1.04	545	<1	0.08	21	510	<3	0.09	<5	3	<10	<5	10	0.03	<5	42	<5	3	42
65	S8R279561	<0.2	1.18	<5	112	<1	<5	0.28	<1	14	34	70	2.48	<5	<0.01	4	8	1.02	420	<1	0.08	23	620	<3	0.08	<5	3	<10	<5	10	0.02	<5	40	<5	3	44
66	S8R279562	<0.2	1.23	<5	104	<1	<5	0.31	<1	15	50	68	2.40	<5	<0.01	4	8	1.21	360	<1	0.08	31	410	<3	0.07	<5	3	<10	<5	10	0.03	<5	44	<5	3	40
67	S8R279563	<0.2	1.34	<5	162	<1	<5	0.39	<1	18	38	88	3.04	<5	<0.01	4	8	1.14	410	<1	0.08	25	480	<3	0.07	<5	4	<10	<5	12	0.03	<5	60	<5	4	54
68	S8R279564	<0.2	1.74	<5	130	<1	<5	0.36	<1	29	4	100	4.30	<5	0.02	<2	8	1.44	675	<1	0.05	12	730	3	0.06	<5	4	<10	<5	8	0.05	<5	84	<5	2	68
69	S8R279565	<0.2	1.97	10	194	<1	<5	0.34	<1	24	16	86	4.66	<5	<0.01	8	12	1.63	715	<1	0.09	19	520	3	0.05	<5	8	<10	<5	12	0.05	<5	106	<5	7	76
70	S8R279566	0.2	0.87	<5	130	<1	<5	0.31	<1	27	40	54	5.95	<5	<0.01	6	4	0.68	1145	<1	0.08	24	600	<3	0.08	<5	18	<10	<5	8	<0.01	<5	154	<5	12	

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
71	S8R279567	0.4	2.28	10	68	<1	<5	0.28	<1	24	8	76	4.56	<5	0.03	6	14	1.38	1105	<1	0.08	12	790	<3	0.05	<5	5	<10	<5	6	0.02	<5	60	<5	7	54
72	S8R279568	<0.2	2.38	<5	62	<1	<5	0.26	<1	22	232	50	3.41	<5	0.03	<2	16	2.60	1120	<1	0.08	95	590	<3	0.06	<5	7	<10	<5	6	0.04	<5	70	<5	4	38
73	S8R279569	<0.2	1.56	<5	46	<1	<5	0.08	<1	20	6	56	2.94	<5	0.03	<2	14	1.03	760	<1	0.08	4	390	<3	0.05	<5	2	<10	<5	4	0.04	<5	40	<5	1	34
74	S8R279570	<0.2	2.17	5	116	<1	<5	0.10	<1	16	18	108	3.63	<5	0.04	6	16	1.07	450	<1	0.08	12	310	<3	0.06	<5	3	<10	<5	8	0.05	<5	66	<5	2	52
75	S8R279571	<0.2	2.26	<5	64	<1	<5	0.14	<1	22	8	114	4.15	<5	0.04	<2	14	1.44	695	<1	0.06	7	430	<3	0.06	<5	2	<10	<5	4	0.04	<5	60	<5	2	82
76	S8R279572	<0.2	1.89	5	124	<1	<5	0.12	<1	13	18	44	3.18	<5	0.04	6	14	0.92	435	<1	0.09	11	420	<3	0.06	<5	2	<10	<5	8	0.03	<5	58	<5	2	64
77	S8R279573	<0.2	2.02	10	68	<1	<5	0.14	<1	19	16	38	3.64	<5	0.04	4	16	1.14	975	<1	0.08	10	500	<3	0.07	<5	3	<10	<5	6	0.04	<5	66	<5	2	50
78	S8R279574	<0.2	2.20	<5	60	<1	<5	0.11	<1	20	12	58	3.86	<5	0.03	<2	14	1.61	875	<1	0.07	9	240	<3	0.07	<5	3	<10	<5	4	0.05	<5	58	<5	2	50
79	S8R279575	<0.2	2.15	<5	48	<1	<5	0.12	<1	23	16	44	4.08	<5	0.02	<2	12	1.37	1095	<1	0.08	10	500	<3	0.06	<5	2	<10	<5	4	0.06	<5	58	<5	1	54
80	S8R279576	<0.2	1.93	5	164	<1	<5	0.22	<1	16	32	48	3.80	<5	0.03	8	14	1.13	770	<1	0.08	22	610	<3	0.07	<5	8	<10	<5	10	0.03	<5	80	<5	9	62
81	S8R279577	<0.2	1.68	5	106	<1	<5	0.17	<1	10	18	26	2.94	<5	0.03	6	12	0.89	360	<1	0.07	9	500	<3	0.07	<5	2	<10	<5	8	0.02	<5	62	<5	3	50
82	S8R279578	<0.2	1.30	<5	52	<1	<5	0.27	<1	6	6	12	2.21	<5	0.02	2	12	0.73	535	<1	0.08	1	1080	<3	0.06	<5	1	<10	<5	6	0.01	<5	16	<5	2	56
83	S8R279579	<0.2	2.22	10	148	<1	<5	0.07	<1	27	22	98	4.22	<5	0.03	6	14	1.24	650	<1	0.08	23	270	6	0.08	<5	8	<10	<5	6	0.02	<5	58	<5	6	134
84	S8R279580	<0.2	2.03	<5	110	<1	<5	0.16	<1	20	16	68	3.08	<5	0.02	6	12	1.29	670	<1	0.06	17	160	<3	0.07	<5	6	<10	<5	6	0.02	<5	60	<5	6	66
85	S8R279581	0.2	1.61	5	156	<1	<5	0.14	<1	17	18	40	3.67	<5	0.03	6	10	0.73	620	1	0.08	11	500	6	0.07	<5	4	<10	<5	6	0.02	<5	48	<5	4	96
86	S8R279582	<0.2	1.91	5	96	<1	<5	0.14	<1	27	8	74	4.69	<5	0.02	4	12	1.26	1100	<1	0.08	9	590	6	0.07	<5	6	<10	<5	6	<0.01	<5	50	<5	7	148
87	S8R279583	<0.2	1.93	5	108	<1	<5	0.16	<1	24	10	8	4.43	<5	0.02	6	10	1.24	1020	<1	0.08	11	610	6	0.08	<5	6	<10	<5	8	<0.01	<5	52	<5	7	136
88	S8R279584	<0.2	1.93	5	108	<1	<5	0.16	<1	24	10	8	4.43	<5	0.02	6	10	1.24	1020	<1	0.08	11	610	6	0.08	<5	6	<10	<5	8	<0.01	<5	52	<5	7	136

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFILL PDF Editor with Free Writer and Tools

187	S8R288001	0.2	2.47	<5	122	<1	<5	0.63	<1	23	32	72	4.73	<5	0.05	8	14	1.64	770	1	0.06	23	640	3	0.10	<5	11	<10	<5	18	0.05	<5	96	<5	10	94
188	S8R288002	<0.2	2.35	<5	208	<1	<5	0.61	<1	23	20	56	4.37	<5	0.27	4	16	1.94	960	<1	0.07	16	570	<3	0.10	<5	8	<10	<5	16	0.13	<5	114	<5	4	76
189	S8R288003	0.2	2.19	5	204	<1	<5	1.20	<1	20	34	54	3.54	<5	0.06	6	14	1.53	800	<1	0.07	22	560	<3	0.12	<5	5	<10	<5	28	0.07	<5	78	<5	5	76
190	S8R288004	<0.2	1.83	<5	192	<1	<5	0.78	<1	17	24	34	3.11	<5	0.05	6	12	1.32	715	<1	0.05	16	590	<3	0.11	<5	5	<10	<5	20	0.07	<5	68	<5	4	64

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
191	S8R288005	<0.2	1.75	<5	192	<1	<5	0.60	<1	16	20	26	3.08	<5	0.04	6	12	1.26	675	<1	0.07	13	420	<3	0.10	<5	5	<10	<5	18	0.08	<5	74	<5	4	60
192	S8R288006	<0.2	1.78	<5	200	<1	<5	0.43	<1	15	20	26	3.11	<5	0.05	8	12	1.16	710	<1	0.07	14	580	<3	0.10	<5	5	<10	<5	14	0.07	<5	68	<5	4	64
193	S8R288007	<0.2	1.55	<5	108	<1	<5	0.35	<1	9	14	14	3.01	<5	0.09	8	10	0.80	365	<1	0.07	8	300	<3	0.09	<5	4	<10	<5	16	0.10	<5	60	<5	4	52
194	S8R288008	0.2	1.70	<5	256	<1	<5	0.60	<1	11	18	24	3.00	<5	0.11	12	12	1.09	470	<1	0.07	11	680	<3	0.09	<5	5	<10	<5	18	0.05	<5	48	<5	10	64
195	S8R288009	0.4	1.95	10	634	<1	<5	1.04	<1	14	16	34	3.57	<5	0.09	22	18	0.78	1400	1	0.06	14	860	3	0.13	<5	10	<10	<5	50	0.02	<5	66	<5	40	64
196	S8R288010	<0.2	1.40	<5	248	<1	<5	0.28	<1	13	24	22	2.87	<5	0.24	6	10	0.97	575	<1	0.06	11	350	6	0.08	<5	3	<10	<5	12	0.08	<5	54	<5	6	56
197	S8R288011	<0.2	1.13	<5	132	<1	<5	0.14	<1	8	18	22	2.33	<5	0.31	8	6	0.64	310	<1	0.07	8	260	<3	0.09	<5	3	<10	<5	6	0.12	<5	64	<5	4	42
198	S8R288012	<0.2	1.48	<5	170	<1	<5	0.33	<1	11	14	16	2.62	<5	0.28	4	8	1.07	505	<1	0.06	9	520	<3	0.09	<5	2	<10	<5	12	0.08	<5	46	<5	3	60
199	S8R288013	<0.2	2.11	<5	444	<1	<5	0.34	<1	19	20	28	4.32	<5	0.72	2	12	1.51	720	<1	0.07	11	670	<3	0.09	<5	5	<10	<5	8	0.17	<5	132	<5	3	68
200	S8R288014	<0.2	0.89	<5	70	<1	<5	0.37	<1	5	8	8	1.63	<5	0.20	6	4	0.54	285	<1	0.06	5	960	<3	0.10	<5	2	<10	<5	12	0.07	<5	26	<5	3	42
201	S8R288015	<0.2	1.55	<5	132	<1	<5	0.40	<1	15	22	24	2.77	<5	0.11	4	8	1.24	750	<1	0.06	13	560	<3	0.10	<5	4	<10	<5	14	0.07	<5	62	<5	3	56
202	S8R288016	<0.2	1.85	<5	122	<1	<5	0.48	<1	17	26	30	3.32	<5	0.07	4	10	1.44	800	<1	0.05	17	650	<3	0.10	<5	5	<10	<5	14	0.06	<5	66	<5	3	66
203	S8R288017	0.2	1.99	<5	126	<1	<5	0.44	<1	18	56	44	3.82	<5	0.02	6	10	1.48	560	<1	0.07	32	560	9	0.10	<5	9	<10	<5	14	0.03	<5	86	<5	5	78
204	S8R288018	0.2	2.01	<5	152	<1	<5	0.47	<1	20	30	54	3.54	<5	<0.01	8	10	1.31	590	<1	0.08	23	640	6	0.09	<5	7	<10	<5	14	0.05	<5	66	<5	7	88
205	S8R288019	0.4	2.08	10	110	<1	<5	0.56	<1	18	34	84	4.49	<5	<0.01	8	10	1.45	685	<1	0.07	28	670	15	0.10	<5	12	<10	<5	12	0.04	<5	90	<5	13	96
206	S8R288020	<0.2	2.20	5	114	<1	<5	0.26	<1	17	34	66	3.48	<5	<0.01	8	10	1.50	755	<1	0.06	21	540	12	0.09	<5	4	<10	<5	10	0.07	<5	54	<5	8	84
207	S8R288021	<0.2	2.07	<5	112	<1	<5	0.36	<1	15	18	24	3.27	<5	<0.01	8	10	1.36	615	<1	0.06	14	510	3	0.09	<5	3	<10	<5	14	0.07	<5	52	<5	5	58
208	S8R288022	<0.2	2.21	<5	62	<1	<5	0.28	<1	18	14	38	2.72	<5	<0.01	4	10	1.71	625	<1	0.06	13	550	<3	0.09	<5	2	<10	<5	12	0.08	<5	58	<5	2	60
209	S8R288023	<0.2	2.12	5	64	<1	<5	0.23	<1	17	28	40	3.24	<5	<0.01	4	10	1.50	465	<1	0.06	19	250	<3	0.09	<5	3	<10	<5	10	0.10	<5	58	<5	2	50
210	S8R288024	<0.2	2.29	5	58	<1	<5	0.26	<1	17	24	34	3.53	<5	<0.01	4	12	1.56	490	<1	0.07	18	350	<3	0.09	<5	2	<10	<5	10	0.11	<5	54	<5	2	52
211	S8R288025	<0.2	1.98	5	74	<1	<5	0.21	<1	13	16	32	3.24	<5	0.10	6	10	1.09	590	<1	0.07	11	320	12	0.05	<5	3	<10	<5	10	0.13	<5	46	<5	3	68
212	S8R288026	<0.2	1.99	<5	70	<1	<5	0.18	<1	13	12	26	3.36	<5	0.08	6	12	1.28	585	<1	0.06	10	330	12	0.05	<5	3	<10	<5	10	0.10	<5	48	<5	3	70
213	S8R288027	0.2	1.34	30	102	<1	<5	0.31	<1	14	16	28	2.95	<5	0.22	10	8	0.95	520	1	0.07	18	1060	12	0.06	<5	3	<10	<5	12	0.09	<5	36	<5	6	82
214	S8R288028	<0.2	1.60	<5	180	<1	<5	0.32	<1	13	18	30	2.85	<5	0.11	8	8	1.06	565	<1	0.07	12	520	12	0.08	<5	4	<10	<5	12	0.06	<5	56	<5	4	58
215	S8R288029	0.6	1.84	<5	174	<1	<5	0.48	<1	19	18	44	3.35	<5	0.09	4	10	1.35	840	<1	0.07	15	630	21	0.08	<5	4	<10	<5	14	0.05	<5	64	<5	3	70
216	S8R288030	<0.2	1.74	<5	164	<1	<5	0.48	<1	18	16	42	3.16	<5	0.10	4	8	1.29	815	<1	0.08	15	600	15	0.08	<5	3	<10	<5	14	0.05	<5	62	<5	3	76
217	S8R288031	<0.2	1.82	<5	180	<1	<5	0.53	<1	17	18	46	3.24	<5	0.09	4	8	1.36	610	<1	0.06	15	590	12	0.08	<5	4	<10	<5	14	0.05	<5	64	<5	3	66
218	S8R288032	<0.2	2.05	<5	140	<1	<5	0.31	<1	19	20	42	3.72	<5	0.11	6	10	1.44	660	<1	0.06	15	570	12	0.07	<5	3	<10	<5	10	0.06	<5	74	<5	3	72
219	S8R288033	<0.2	2.12	5	132	<1	<5	0.39	<1	25	34	76	4.22	<5	0.33	<2	10	2.11	840	<1	0.07	24	740	9	0.04	<5	3	<10	<5	8	0.14	<5	86	<5	3	70
220	S8R288034	<0.2	1.95	<5	164	<1	<5	0.50	<1	14	16	30	3.33	<5	0.10	6	10	1.21	670	<1	0.06	12	510	15	0.08	<5	3	<10	<5	14	0.05	<5	58	<5	3	68
221	S8R288035	<0.2	2.10	<5	132	<1	<5	0.46	<1	16	18	42	3.53	<5	0.09	8	10	1.25	600	<1	0.07	14	570	12	0.06	<5	3	<10	<5	14	0.05	<5	62	<5	4	74
222	S8R288036	<0.2	1.94	<5	96	<1	<5	0.28	<1	14	18	36	3.45	<5	0.10	8	10	1.26	520	<1	0.08	14	590	9	0.05	<5	3	<10	<5	12	0.09	<5	60	<5	3	82
223	S8R288037	<0.2	2.23	<5	86	<1	<5	0.23	<1	16	16	46	3.77	<5	0.08	6	10	1.50	540	<1	0.06	12	390	12	0.05	<5	3	<10	<5	8	0.10	<5	62	<5	3	64
224	S8R288038	<0.2	2.41	<5	72	<1	<5	0.27	<1	21	14	64	4.27	<5	0.08	4	10	1.76	665	<1	0.07	12	390	15	0.05	<5	3	<10	<5	8	0.12	<5	68	<5	2	70
225	S8R288039	0.2	2.24	<5	96	<1	<5	0.20	<1	16	18	50	3.95	<5	0.09	6	12	1.35	605	<1	0.07	13	470	42	0.05	<5	3	<10	<5	8	0.10	<5	62	<5	3	66
226	S8R288040	<0.2	2.72	<5	108	<1	<5	0.20	<1	22	22	34	4.41	<5	0.11	6	12	1.58	825	1	0.08	15	430	24	0.06	<5	6	<10	<5	8	0.13	<5	84	<5	3	70
227	S8R288041	0.2	2.20	5	118	<1	<5	0.20	<1	14	20	50	3.84	<5	0.10	8	14	1.18	545	<1	0.07	13	460	48	0.07	<5	3	<10	<5	8	0.09	<5	62	<5	3	64
228	S8R288042	<0.2	2.64	<5	34	<1	<5	0.19	<1	21	14	28	4.66	<5	0.07	2	12	1.99	735	<1	0.05	10	350	18	0.05	<5	3	<10	<5	6	0.10	<5	84	<5	2	72
229	S8R288043	<0.2	2.35	5	106	<1	<5	0.18	<1	14	28	42	3.37	<5	0.07	8	12	1.34	520	<1	0.08	18	310	12	0.05	<5	4	<10	<5	10	0.10	<5	62	<5	3	60
230	S8R288044	0.2	2.47	5	86	<1	<5	0.20	<1	15	34	112	3.93	<5	0.06	8	12	1.49	830	<1	0.05	21	370	12	0.05	<5	6	<10	<5	8	0.10	<5	62	<5		

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
231	S8R288045	<0.2	2.50	<5	82	<1	<5	0.21	<1	15	30	110	4.06	<5	0.06	8	14	1.52	810	<1	0.07	20	380	12	0.06	<5	5	<10	<5	8	0.10	<5	66	<5	5	70
232	S8R288046	<0.2	2.08	<5	88	<1	<5	0.23	<1	12	18	30	3.30	<5	0.06	6	12	1.41	665	<1	0.08	13	620	12	0.05	<5	4	<10	<5	8	0.10	<5	52	<5	5	60
233	S8R288047	0.2	2.43	<5	66	<1	<5	0.15	<1	14	20	46	3.60	<5	0.03	4	14	1.75	910	<1	0.07	12	450	12	0.02	<5	4	<10	<5	6	0.05	<5	58	<5	4	84
234	S8R288048	<0.2	2.58	5	76	<1	<5	0.14	<1	19	38	64	4.16	<5	0.04	6	14	1.83	1265	<1	0.08	24	640	60	0.04	<5	8	<10	<5	6	0.03	<5	64	<5	6	194
235	S8R288049	0.4	3.20	10	68	<1	<5	0.14	<1	21	116	108	4.96	<5	0.05	4	16	2.73	1365	<1	0.07	59	450	24	0.05	<5	7	<10	<5	4	0.05	<5	76	<5	4	750
236	S8R288050	<0.2	2.40	<5	42	<1	<5	0.14	<1	20	20	56	4.02	<5	0.03	4	12	1.88	845	<1	0.07	15	320	12	0.05	<5	5	<10	<5	8	0.02	<5	58	<5	5	88

QC DATA:**Repeat:**

1	S8R279497	0.2	1.28	<5	70	<1	<5	0.32	<1	17	8	86	3.59	<5	0.11	8	8	0.96	790	<1	0.07	9	740	<3	0.07	<5	10	<10	<5	6	<0.01	<5	86	<5	10	54
10	S8R279506	0.4	1.18	20	220	<1	<5	0.37	<1	12	24	26	2.52	<5	0.22	12	10	1.02	435	1	0.09	19	710	6	0.05	<5	4	<10	<5	16	0.05	<5	34	<5	6	74
19	S8R279515	<0.2	2.43	<5	66	<1	<5	0.07	<1	20	4	56	5.24	<5	<0.01	2	12	1.77	1065	<1	0.07	5	220	<3	0.06	<5	7	<10	<5	4	0.02	<5	124	<5	4	74
36	S8R279524	<0.2	0.90	<5	100	<1	<5	0.18	<1	7	10	10	1.87	<5	0.02	6	6	0.62	215	<1	0.08	8	580	<3	0.05	<5	2	<10	<5	10	0.04	<5	34	<5	2	46
45	S8R279532	<0.2	1.66	<5	72	<1	<5	0.24	<1	17	36	34	3.12	<5	<0.01	2	8	1.71	790	<1	0.09	24	750	3	0.04	<5	3	<10	<5	6	0.03	<5	56	<5	2	74
54	S8R279541	<0.2	0.07	<5	22	<1	<5	>10	<1	2	<2	<2	0.70	<5	<0.01	<2	2	>10	235	<1	0.05	4	250	<3	0.03	<5	1	<10	<5	56	<0.01	<5	4	<5	1	16
71	S8R279550	0.2	2.20	10	66	<1	<5	0.28	<1	23	8	76	4.43	<5	0.03	4	12	1.34	1090	<1	0.07	11	820	<3	0.07	<5	4	<10	<5	6	0.02	<5	58	<5	7	52
80	S8R279567	<0.2	1.87	5	158	<1	<5	0.20	<1	16	30	48	3.72	<5	0.03	8	12	1.09	775	<1	0.07	21	580	<3	0.08	<5	8	<10	<5	10	0.03	<5	78	<5	8	60
89	S8R279576	<0.2	1.28	<5	122	<1	<5	0.09	<1	5	6		1.94	<5	0.03	24	14	0.53	290	<1	0.08	3	290	6	0.07	<5	1	<10	<5	4	<0.01	<5	18	<5	6	46

194	S8R288008	0.2	1.84	<5	264	<1	<5	0.62	<1	12	18	26	3.11	<5	0.12	12	14	1.14	490	<1	0.08	12	710	<3	0.10	<5	5	<10	<5	22	0.06	<5	50	<5	10	68
211	S8R288025	0.2	1.96	5	74	<1	<5	0.19	<1	13	14	30	3.23	<5	0.12	6	10	1.10	990	<1	0.07	11	330	15	0.03	<5	3	<10	<5	10	0.13	<5	46	<5	2	66
220	S8R288034	<0.2	1.91	<5	160	<1	<5	0.48	<1	14	16	30	3.26	<5	0.08	6	10	1.18	655	<1	0.07	12	510	15	0.07	<5	3	<10	<5	14	0.05	<5	58	<5	3	66
229	S8R288043	<0.2	2.26	5	104	<1	<5	0.17	<1	14	26	42	3.30	<5	0.05	8	12	1.29	505	<1	0.07	17	300	12	0.04	<5	4	<10	<5	8	0.10	<5	60	<5	3	58

Standard:


TILL3	1.6	1.00	80	40	<1	<5	0.55	<1	12	68	22	2.10	<5	0.08	14	18	0.56	355	<1	0.10	32	470	18	0.07	<5	4	<10	<5	16	0.08	<5	36	<5	6	40
TILL3	1.6	1.00	75	40	<1	<5	0.54	<1	11	64	22	2.06	<5	0.06	14	18	0.56	350	<1	0.11	32	460	18	0.07	<5	4	<10	<5	20	0.07	<5	38	<5	6	42
TILL3	1.4	1.10	75	44	<1	<5	0.57	<1	11	66	20	2.04	<5	0.07	14	16	0.59	365	<1	0.10	32	480	21	0.08	<5	3	<10	<5	18	0.07	<5	36	<5	6	36
TILL3	1.6	1.10	75	40	<1	<5	0.56	<1	12	70	22	2.07	<5	0.04	14	18	0.59	355	<1	0.09	34	460	21	0.08	<5	4	<10	<5	16	0.08	<5	38	<5	6	38
TILL3	1.6	1.03	80	42	<1	<5	0.56	<1	12	70	22	2.10	<5	0.06	14	18	0.60	340	<1	0.09	34	460	18	0.09	<5	4	<10	<5	18	0.08	<5	36	<5	7	40
TILL3	1.6	1.06	75	38	<1	<5	0.55	<1	11	64	22	2.07	<5	0.06	14	16	0.61	365	<1	0.09	32	490	21	0.05	<5	4	<10	<5	18	0.08	<5	38	<5	6	44

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/mb/el

dl/msr8167AS/msr8167BS/msr8167CS/msr8167DS

XLS/11



ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

CERTIFICATE OF ANALYSIS AW 2011-8168

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

21-Sep-11

No. of samples received: 309
Sample Type: Soil
Project: Dawson Area
Submitted by: All Terrane Mineral Expl.

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
33	S8R278983	5
34	S8R278984	10
35	S8R278985	5
36	S8R278986	15
37	S8R278987	<5
38	S8R278988	<5
39	S8R278989	<5
40	S8R278990	5
41	S8R278991	<5
42	S8R278992	<5
43	S8R278993	<5

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

116	S8R281354	5
117	S8R281355	10
118	S8R281356	5
119	S8R281357	<5
120	S8R281358	<5
121	S8R281359	30
122	S8R281360	5
123	S8R281361	<5
124	S8R281362	<5
125	S8R281363	<5
126	S8R281364	<5



Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
127	S8R281365	5
128	S8R281366	5
129	S8R281367	<5
130	S8R281368	<5
131	S8R281369	<5
132	S8R281370	10
133	S8R281371	5
134	S8R281372	5
135	S8R281373	5
136	S8R281374	<5
137	S8R281375	5
138	S8R281376	5
139	S8R281377	10
140	S8R281378	5
141	S8R281379	5
142	S8R281380	5
143	S8R281381	20
144	S8R281382	<5
145	S8R281383	20
146	S8R281384	5
147	S8R281385	5
148	S8R281386	5
149	S8R281387	5
150	S8R281388	5
151	S8R281389	5
152	S8R281390	10
153	S8R281391	<5
154	S8R281392	5
155	S8R281393	<5
156	S8R281394	<5
157	S8R281395	<5
158	S8R281396	<5
159	S8R281397	<5
160	S8R281398	<5
161	S8R281399	435
162	S8R281400	<5
163	S8R281401	<5
164	S8R281402	<5
165	S8R281403	<5
166	S8R281404	<5
167	S8R281405	<5
168	S8R281406	<5
169	S8R281407	<5
170	S8R281408	5
171	S8R281409	<5
172	S8R281410	<5
173	S8R281411	<5

PDFill PDF Editor with Free Writer and Tools



Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
174	S8R281412	<5
175	S8R281413	<5
176	S8R281414	<5
177	S8R281415	15
178	S8R281416	<5
179	S8R281417	<5
180	S8R281418	5
181	S8R281419	<5
182	S8R281420	10
183	S8R281421	10
184	S8R281422	<5
185	S8R281423	<5
186	S8R281424	<5
187	S8R281425	<5
188	S8R281426	<5
189	S8R281427	<5
190	S8R281428	15
191	S8R281429	25
192	S8R281430	10
193	S8R281431	5
194	S8R281432	<5
195	S8R281433	<5
196	S8R281434	<5
197	S8R281435	5
198	S8R281436	<5
199	S8R281437	<5
200	S8R281438	<5
201	S8R281439	<5
202	S8R281440	<5
203	S8R281441	5
204	S8R281442	<5
205	S8R281443	<5
206	S8R281444	5

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

QC DATA:

Repeat:

124	S8R281362	<5
133	S8R281371	<5
141	S8R281379	5
150	S8R281388	15
159	S8R281397	<5
168	S8R281406	5
176	S8R281414	<5
185	S8R281423	5
194	S8R281432	5
203	S8R281441	<5

PDFill PDF Editor with Free Writer and Tools

Standard:

OXE86	615
OXE86	595
OXE86	605
OXE86	605
OXE86	595
OXE86	595

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8168

21-Sep-11

ET #.	Tag #	Au (ppb)
OXE86		615
OXE86		610

FA Geochem/AA Finish

NM/sa/el
XLS/11


ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

PDFill PDF Editor with Free Writer and Tools

21-Sep-11

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8168

Kestrel Gold Corp.
#8-46225 Rancho Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 309
Sample Type: Soil
Project: Dawson Area
Submitted by: All Terrane Mineral Expl.

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFILL PDF Editor with Free Writer and Tools

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

116	S8R281354	<0.2	2.37	5	156	<1	<5	0.22	<1	16	24	44	4.20	<5	0.12	12	16	1.40	610	<1	0.05	18	340	12	0.13	<5	8	<10	<5	12	0.03	<5	94	<5	7	60
117	S8R281355	0.4	1.94	5	136	<1	<5	0.15	<1	13	26	42	3.21	<5	0.11	10	14	1.00	430	<1	0.05	19	290	9	0.12	<5	4	<10	<5	12	0.04	<5	70	<5	5	52
118	S8R281356	<0.2	2.38	10	140	<1	<5	0.08	<1	18	32	56	3.95	<5	0.12	10	16	1.28	710	<1	0.05	23	200	21	0.12	<5	6	<10	<5	8	0.04	<5	70	<5	4	66
119	S8R281357	<0.2	2.59	<5	16	<1	<5	0.04	<1	21	32	16	5.18	<5	0.07	<2	20	2.57	785	<1	0.05	22	330	9	0.09	<5	5	<10	<5	<2	0.05	<5	96	<5	1	74
120	S8R281358	<0.2	3.00	<5	54	<1	<5	0.04	<1	17	18	36	5.15	<5	0.06	4	18	2.60	635	<1	0.05	17	210	9	0.08	<5	9	<10	<5	4	0.01	<5	106	<5	4	70

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
121	S8R281359	0.2	2.67	<5	80	<1	<5	0.07	<1	16	40	86	4.33	<5	0.08	12	16	1.59	775	<1	0.05	32	290	12	0.10	<5	6	<10	<5	6	0.01	<5	46	<5	3	242
122	S8R281360	0.2	2.77	5	252	<1	<5	0.28	<1	17	52	48	3.89	<5	0.12	16	18	1.28	1365	<1	0.05	30	360	9	0.14	<5	8	<10	<5	14	0.05	<5	84	<5	9	96
123	S8R281361	0.8	2.49	5	140	<1	<5	0.19	<1	14	46	18	3.70	<5	0.12	8	16	1.25	655	<1	0.05	20	270	12	0.13	<5	5	<10	<5	12	0.06	<5	98	<5	2	52
124	S8R281362	<0.2	2.60	<5	74	<1	<5	0.17	<1	24	326	46	3.68	<5	0.11	6	14	3.25	725	<1	0.05	98	280	6	0.09	<5	5	<10	<5	8	0.09	<5	86	<5	6	54
125	S8R281363	<0.2	2.49	<5	82	<1	<5	0.32	<1	27	66	48	4.45	<5	0.07	6	12	2.72	855	<1	0.05	34	350	<3	0.09	<5	4	<10	<5	18	0.13	<5	108	<5	5	62
126	S8R281364	<0.2	2.89	<5	56	<1	<5	0.32	<1	29	72	46	4.74	<5	0.06	2	14	3.33	1030	<1	0.05	39	540	<3	0.08	<5	4	<10	<5	20	0.10	<5	106	<5	2	76
127	S8R281365	<0.2	2.37	5	112	<1	<5	0.19	<1	18	32	34	3.82	<5	0.07	6	12	1.81	735	<1	0.05	21	260	9	0.09	<5	4	<10	<5	12	0.10	<5	80	<5	3	88
128	S8R281366	<0.2	2.00	5	146	<1	<5	0.15	<1	14	24	22	3.21	<5	0.09	8	10	1.22	710	<1	0.05	14	570	6	0.10	<5	2	<10	<5	12	0.05	<5	70	<5	3	60
129	S8R281367	<0.2	2.05	5	168	<1	<5	0.20	<1	12	30	26	3.20	<5	0.09	10	12	1.10	435	<1	0.05	19	390	9	0.11	<5	3	<10	<5	14	0.07	<5	68	<5	3	70
130	S8R281368	<0.2	2.17	5	124	<1	<5	0.17	<1	13	26	28	3.44	<5	0.08	8	12	1.43	515	<1	0.05	17	280	15	0.09	<5	3	<10	<5	10	0.08	<5	72	<5	3	70
131	S8R281369	<0.2	2.12	5	134	<1	<5	0.20	<1	13	32	28	3.37	<5	0.08	8	12	1.37	580	<1	0.05	19	450	15	0.09	<5	3	<10	<5	12	0.07	<5	70	<5	3	64
132	S8R281370	0.2	2.15	5	128	<1	<5	0.16	<1	13	32	32	3.51	<5	0.08	8	14	1.32	655	<1	0.05	21	430	6	0.10	<5	3	<10	<5	10	0.06	<5	70	<5	3	60
133	S8R281371	<0.2	1.97	5	132	<1	<5	0.16	<1	13	26	26	3.37	<5	0.07	8	12	1.18	485	<1	0.05	17	460	6	0.09	<5	3	<10	<5	10	0.05	<5	72	<5	3	60
134	S8R281372	<0.2	2.34	5	146	<1	<5	0.18	<1	13	28	24	3.66	<5	0.09	8	12	1.44	495	<1	0.05	19	310	6	0.11	<5	3	<10	<5	12	0.08	<5	82	<5	3	64
135	S8R281373	<0.2	2.39	5	126	<1	<5	0.17	<1	13	30	32	3.72	<5	0.09	8	12	1.48	420	<1	0.06	19	470	24	0.12	<5	3	<10	<5	12	0.07	<5	82	<5	3	78
136	S8R281374	<0.2	2.74	5	98	<1	<5	0.19	<1	27	26	56	4.71	<5	0.09	4	12	2.21	1545	1	0.05	26	550	9	0.10	<5	4	<10	<5	8	0.05	<5	70	<5	3	160
137	S8R281375	<0.2	2.31	<5	92	<1	<5	0.19	<1	18	22	40	3.79	<5	0.08	6	10	1.66	625	<1	0.05	16	550	6	0.09	<5	3	<10	<5	12	0.07	<5	78	<5	3	96
138	S8R281376	<0.2	1.85	10	154	<1	<5	0.18	<1	12	30	28	3.66	<5	0.10	10	12	0.95	440	<1	0.05	19	470	6	0.12	<5	3	<10	<5	14	0.06	<5	66	<5	4	58
139	S8R281377	<0.2	1.59	5	146	<1	<5	0.16	<1	7	24	20	2.19	<5	0.14	10	10	0.69	220	<1	0.05	14	620	6	0.14	<5	1	<10	<5	14	0.03	<5	54	<5	3	46
140	S8R281378	<0.2	1.97	5	166	<1	<5	0.16	<1	10	30	26	3.03	<5	0.16	12	14	0.88	325	<1	0.05	18	490	15	0.13	<5	3	<10	<5	14	0.05	<5	64	<5	4	56
141	S8R281379	<0.2	1.83	5	146	<1	<5	0.14	<1	11	28	34	2.95	<5	0.04	12	16	0.94	400	<1	0.07	19	340	6	0.02	<5	4	<10	<5	10	0.07	<5	56	<5	5	72
142	S8R281380	<0.2	1.93	5	138	<1	<5	0.13	<1	14	34	38	3.28	<5	0.04	14	18	1.13	520	<1	0.07	22	320	6	<0.01	<5	5	<10	<5	10	0.06	<5	58	<5	6	82
143	S8R281381	<0.2	2.12	5	148	<1	<5	0.11	<1	16	28	50	3.66	<5	0.04	14	18	1.09	650	<1	0.07	20	310	9	<0.01	<5	6	<10	<5	8	0.05	<5	64	<5	7	108
144	S8R281382	<0.2	2.06	10	124	<1	<5	0.10	<1	12	30	42	3.32	<5	0.05	12	18	1.02	470	<1	0.07	21	290	12	<0.01	<5	5	<10	<5	8	0.05	<5	62	<5	5	104
145	S8R281383	<0.2	2.18	5	146	<1	<5	0.12	<1	11	26	36	3.31	<5	0.04	10	16	0.85	505	<1	0.07	17	370	12	<0.01	<5	5	<10	<5	8	0.05	<5	58	<5	4	78
146	S8R281384	<0.2	3.24	<5	56	<1	<5	0.09	<1	27	58	62	5.15	<5	0.02	4	22	2.65	1011	<1	0.06	35	370	12	0.01	<5	9	<10	<5	4	0.04	<5	88	<5	4	172
147	S8R281385	<0.2	2.88	5	86	<1	<5	0.08	<1	28	48	86	4.80	<5	0.03	6	20	2.00	865	<1	0.06	34	280	12	0.01	<5	10	<10	<5	6	0.05	<5	98	<5	4	118
148	S8R281386	0.6	2.83	<5	34	<1	<5	0.20	2	24	66	44	4.53	<5	0.02	<2	20	2.43	1555	<1	0.06	35	920	9	0.02	<5	8	<10	<5	4	0.06	<5	96	<5	3	372
149	S8R281387	<0.2	2.10	10	128	<1	<5	0.12	<1	14	30	58	3.20	<5	0.04	10	18	1.01	515	<1	0.07	23	170	9	0.01	<5	4	<10	<5	8	0.07	<5	62	<5	3	124
150	S8R281388	<0.2	2.38	<5	114	<1	<5	0.22	<1	18	42	62	4.03	<5	0.03	6	20	1.73	785	<1	0.06	25	450	9	0.03	<5	7	<10	<5	10	0.05	<5	78	<5	4	152
151	S8R281389	0.2	2.28	5	126	<1	<5	0.24	<1	17	36	50	3.93	<5	0.03	8	20	1.59	760	<1	0.06	23	640	18	0.03	<5	7	<10	<5	10	0.03	<5	60	<5	6	168
152	S8R281390	<0.2	2.15	5	152	<1	<5	0.23	<1	14	34	40	3.56	<5	0.03	10	20	1.42	630	<1	0.07	23	520	15	0.03	<5	7	<10	<5	10	0.04	<5	62	<5	7	110
153	S8R281391	<0.2	2.00	<5	108	<1	<5	0.32	<1	11	22	32	3.38	<5	0.03	6	20	1.22	575	<1	0.06	13	530	18	0.03	<5	5	<10	<5	10	0.03	<5	52	<5	5	120
154	S8R281392	<0.2	0.60	<5	48	<1	<5	0.98	<1	24	16	54	4.59	<5	0.04	<2	6	0.30	940	<1	0.06	28	600	<3	0.05	<5	17	<10	<5	18	<0.01	<5	86	<5	5	72
155	S8R281393	<0.2	1.13	<5	126	<1	<5	0.16	<1	6	10	12	2.22	<5	0.14	10	10	0.69	270	<1	0.06	7	320	6	0.04	<5	3	<10	<5	8	0.08	<5	42	<5	5	50
156	S8R281394	<0.2	1.40	<5	134	<1	<5	0.29	<1	11	8	16	3.07	<5	0.26	6	12	0.96	495	<1	0.06	6	770	<3	0.04	<5	3	<10	<5	8	0.09	<5	44	<5	5	66
157	S8R281395	<0.2	1.60	<5	160	<1	<5	0.34	<1	13	24	32	2.76	<5	0.07	8	12	1.20	445	<1	0.07	17	510	<3	0.03	<5	3	<10	<5	12	0.08	<5	56	<5	4	60
158	S8R281396	<0.2	1.75	<5	178	<1	<5	0.37	<1	15	28	42	2.93	<5	0.07	6	12	1.34	380	<1	0.07	20	470	<3	0.03	<5	3	<10	<5	12	0.07	<5	58	<5	4	56
159	S8R281397	<0.2	1.75	<5	82	<1	<5	0.32	<1	18	28	44	3.41	<5	0.16	2	14	1.62	560	<1	0.06	18	540	<3	0.04	<5	3	<10	<5	10	0.11	<5	78	<5	2	56
160	S8R281398	<0.2	1.80	<5	164	<1	<5	0.35	<1	16	30	54	3.07	<5	0.05	6	12	1.39	495	<1	0.06	21	460	<3	0.04	<5	2	<10	<5							

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
166	S8R281404	<0.2	1.46	<5	52	<1	<5	0.18	<1	12	12	24	2.69	<5	0.04	4	12	1.09	370	<1	0.06	9	330	<3	0.05	<5	1	<10	<5	6	0.07	<5	40	<5	2	44
167	S8R281405	<0.2	1.55	<5	64	<1	<5	0.17	<1	12	14	34	2.71	<5	0.04	4	10	1.03	355	<1	0.07	12	310	<3	0.04	<5	2	<10	<5	8	0.07	<5	46	<5	2	46
168	S8R281406	<0.2	1.62	5	92	<1	<5	0.24	<1	13	16	42	2.97	<5	0.04	6	12	1.01	395	<1	0.07	13	460	<3	0.05	<5	2	<10	<5	10	0.07	<5	50	<5	3	56
169	S8R281407	<0.2	1.91	5	102	<1	<5	0.23	<1	14	18	44	3.29	<5	0.04	8	12	1.25	420	<1	0.07	16	390	3	0.04	<5	3	<10	<5	10	0.09	<5	52	<5	3	60
170	S8R281408	<0.2	2.15	<5	54	<1	<5	0.25	<1	18	18	46	3.87	<5	0.03	4	10	1.75	525	<1	0.06	16	410	<3	0.05	<5	2	<10	<5	8	0.11	<5	58	<5	2	66
171	S8R281409	<0.2	2.24	5	44	<1	<5	0.31	<1	24	20	32	3.84	<5	0.02	2	10	2.21	610	<1	0.07	20	600	<3	0.04	<5	2	<10	<5	6	0.12	<5	46	<5	2	66
172	S8R281410	<0.2	2.96	<5	40	<1	<5	0.22	<1	27	38	58	4.80	<5	0.02	2	14	2.54	1065	<1	0.07	29	700	6	0.04	<5	7	<10	<5	8	0.09	<5	104	<5	3	62
173	S8R281411	<0.2	2.35	<5	32	<1	<5	0.21	<1	21	16	48	3.97	<5	0.02	2	12	1.80	565	<1	0.07	16	360	<3	0.03	<5	3	<10	<5	14	0.11	<5	58	<5	2	66
174	S8R281412	<0.2	2.28	<5	38	<1	<5	0.17	<1	16	12	50	3.65	<5	0.02	2	16	2.02	655	<1	0.06	12	400	3	0.04	<5	3	<10	<5	8	0.11	<5	52	<5	3	66
175	S8R281413	<0.2	2.72	<5	40	<1	<5	0.12	<1	18	24	54	4.22	<5	0.03	2	12	2.42	745	<1	0.06	18	260	3	0.04	<5	5	<10	<5	6	0.11	<5	68	<5	5	78
176	S8R281414	0.4	2.72	5	68	<1	<5	0.13	<1	22	120	52	3.99	<5	0.03	6	12	2.30	685	<1	0.07	53	280	9	0.04	<5	6	<10	<5	8	0.09	<5	86	<5	3	64
177	S8R281415	0.6	1.86	10	160	<1	<5	0.12	<1	10	38	22	3.18	<5	0.04	10	12	0.86	775	<1	0.07	18	480	15	0.04	<5	3	<10	<5	8	0.06	<5	58	<5	4	108
178	S8R281416	<0.2	2.48	<5	64	<1	<5	0.14	<1	16	12	44	4.44	<5	0.02	4	8	1.85	675	<1	0.07	13	180	9	0.04	<5	4	<10	<5	8	0.13	<5	70	<5	4	100
179	S8R281417	0.2	2.61	5	102	<1	<5	0.12	<1	17	30	52	4.14	<5	0.03	6	14	1.86	670	<1	0.06	20	260	9	0.03	<5	6	<10	<5	8	0.05	<5	80	<5	4	108
180	S8R281418	0.2	2.28	5	94	<1	<5	0.10	<1	16	46	58	3.77	<5	0.03	8	12	1.64	620	<1	0.06	23	200	9	0.04	<5	6	<10	<5	8	0.03	<5	62	<5	6	134
181	S8R281419	0.4	2.13	10	116	<1	<5	0.15	<1	18	46	60	3.85	<5	0.03	8	12	1.23	615	1	0.07	25	280	15	0.04	<5	5	<10	<5	8	0.04	<5	60	<5	4	166
182	S8R281420	0.4	2.03	10	132	<1	<5	0.10	<1	15	34	44	3.63	<5	0.03	10	10	0.96	615	1	0.07	17	470	18	0.04	<5	4	<10	<5	8	0.04	<5	62	<5	5	152
183	S8R281421	0.4	1.94	10	132	<1	<5	0.08	<1	17	24	44	3.42	<5	0.04	10	10	0.87	535	1	0.07	18	360	12	0.04	<5	4	<10	<5	8	0.05	<5	70	<5	4	118
184	S8R281422	<0.2	1.68	<5	82	<1	<5	0.22	<1	17	32	48	3.38	<5	0.14	2	10	1.47	500	<1	0.06	17	360	<3	0.05	<5	3	<10	<5	6	0.13	<5	60	<5	2	56
185	S8R281423	<0.2	1.58	5	176	<1	<5	0.19	<1	14	18	84	3.12	<5	0.09	8	8	0.95	425	<1	0.07	16	350	3	0.05	<5	4	<10	<5	10	0.07	<5	68	<5	5	52
186	S8R281424	<0.2	1.48	<5	84	<1	<5	0.18	<1	13	14	56	2.93	<5	0.05	1	6	1.01	420	<1	0.06	11	390	3	0.05	<5	1	<10	<5	8	0.06	<5	44	<5	2	48
187	S8R281425	<0.2	1.44	5	62	<1	<5	0.20	<1	12	12	40	2.87	<5	0.04	4	1	0.92	385	<1	0.06	10	380	<3	0.05	<5	1	<10	<5	8	0.09	<5	46	<5	2	46
188	S8R281426	<0.2	2.03	<5	156	<1	<5	0.46	<1	26	12	54	4.05	<5	0.06	4	8	1.51	1515	<1	0.07	12	570	<3	0.07	<5	4	<10	<5	12	0.07	<5	68	<5	3	72
189	S8R281427	<0.2	1.96	<5	138	<1	<5	0.80	<1	29	14	40	4.03	<5	0.05	4	6	1.57	1445	<1	0.07	13	690	<3	0.10	<5	5	<10	<5	16	0.03	<5	74	<5	6	76
190	S8R281428	<0.2	0.72	<5	94	<1	<5	0.65	<1	15	6	44	4.37	<5	0.04	6	<2	0.47	735	<1	0.07	10	870	<3	0.09	<5	11	<10	<5	12	<0.01	<5	74	<5	9	82
191	S8R281429	0.2	1.68	10	148	<1	<5	0.64	<1	16	16	60	3.60	<5	0.05	12	8	1.04	845	<1	0.07	16	650	6	0.08	<5	4	<10	<5	16	0.02	<5	52	<5	10	120
192	S8R281430	0.2	2.34	5	86	<1	<5	0.23	<1	26	12	90	5.10	<5	0.07	4	10	1.92	800	<1	0.06	11	590	<3	0.04	<5	5	<10	<5	8	0.06	<5	92	<5	4	72
193	S8R281431	<0.2	3.08	10	116	<1	<5	0.27	<1	28	12	102	6.10	<5	0.21	<2	14	3.10	900	<1	0.07	13	670	<3	0.04	<5	5	<10	<5	4	0.15	<5	136	<5	3	82
194	S8R281432	<0.2	2.44	5	42	<1	<5	0.22	<1	22	10	50	5.39	<5	0.04	2	8	1.79	875	<1	0.07	18	520	3	0.05	<5	3	<10	<5	8	0.17	<5	96	<5	2	82
195	S8R281433	<0.2	2.16	<5	58	<1	<5	0.15	<1	14	8	32	3.95	<5	0.04	2	6	1.50	555	<1	0.06	7	290	3	0.04	<5	2	<10	<5	6	0.13	<5	68	<5	2	56
196	S8R281434	<0.2	2.34	5	100	<1	<5	0.16	<1	16	18	36	3.88	<5	0.04	6	8	1.50	515	<1	0.07	13	160	<3	0.04	<5	3	<10	<5	6	0.17	<5	66	<5	2	64
197	S8R281435	<0.2	1.94	5	92	<1	<5	0.15	<1	13	16	50	3.22	<5	0.04	6	8	1.17	385	<1	0.07	13	230	3	0.03	<5	3	<10	<5	8	0.11	<5	56	<5	3	54
198	S8R281436	<0.2	1.88	5	108	<1	<5	0.12	<1	11	20	30	3.03	<5	0.04	8	6	0.98	345	<1	0.07	14	230	3	0.03	<5	3	<10	<5	8	0.09	<5	58	<5	3	52
199	S8R281437	<0.2	1.99	<5	98	<1	<5	0.11	<1	14	20	30	3.55	<5	0.04	6	6	1.13	520	<1	0.06	12	350	3	0.03	<5	4	<10	<5	6	0.07	<5	74	<5	2	52
200	S8R281438	<0.2	2.05	<5	88	<1	<5	0.16	<1	17	14	36	3.87	<5	0.04	4	6	1.26	725	<1	0.07	11	480	<3	0.04	<5	4	<10	<5	8	0.06	<5	74	<5	3	62
201	S8R281439	<0.2	2.19	<5	102	<1	<5	0.16	<1	17	18	34	3.82	<5	0.03	4	6	1.56	570	<1	0.06	14	280	3	0.04	<5	4	<10	<5	8	0.10	<5	72	<5	2	60
202	S8R281440	<0.2	2.13	<5	216	<1	<5	0.20	<1	16	16	34	3.53	<5	0.03	6	8	1.28	725	<1	0.06	14	500	3	0.05	<5	4	<10	<5	10	0.05	<5	66	<5	6	58
203	S8R281441	0.2	2.11	<5	200	<1	<5	0.28	<1	13	20	28	3.44	<5	0.03	4	8	1.25	675	1	0.07	14	590	3	0.06	<5	4	<10	<5	12	0.04	<5	62	<5	3	64
204	S8R281442	<0.2	2.09	<5	108	<1	<5	0.41	<1	15	48	36	3.28	<5	0.02	4	8	1.77	795	<1	0.06	25	690	6	0.08	<5	5	<10	<5	12	0.03	<5	64	<5	4	56
205	S8R281443	<0.2	1.91	<5	82	<1	<5	0.31	<1	13	10	38	3.46	<5	0.03	4	4	1.43	615	<1	0.07	11	660	3	0.06	<5	4	<10	<5	10	0.04	<5	54	<5	4	72

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

QC DATA:

Repeat:

124	S8R281362	<0.2	2.67	<5	76	<1	<5	0.18	<1	25	330	48	3.83	<5	0.09	6	14	3.31	740	<1	0.05	103	300	6	0.08	<5	6	<10	<5	8	0.09	<5	88	<5	6	56
141	S8R281379	<0.2	1.80	5	152	<1	<5	0.15	<1	11	28	32	2.92	<5	0.04	12	18	0.93	390	<1	0.06	19	330	6	0.01	<5	4	<10	<5	12	0.07	<5	54	<5	5	70
150	S8R281388	<0.2	2.43	<5	114	<1	<5	0.21	<1	19	42	62	4.08	<5	0.03	6	18	1.77	795	<1	0.07	26	430	9	0.03	<5	7	<10	<5	10	0.05	<5	80	<5	4	158
159	S8R281397	<0.2	1.78	<5	86	<1	<5	0.32	<1	18	30	46	3.47	<5	0.16	2	14	1.66	575	<1	0.06	18	520	3	0.05	<5	3	<10	<5	10	0.11	<5	78	<5	2	58
176	S8R281414	0.4	2.73	5	72	<1	<5	0.13	<1	23	120	52	4.03	<5	0.03	6	10	2.30	595	<1	0.07	53	310	9	0.04	<5	6	<10	<5	8	0.09	<5	88	<5	3	64
185	S8R281423	0.2	1.64	5	180	<1	<5	0.18	<1	14	18	84	3.15	<5	0.09	8	8	0.98	438	<1	0.07	16	380	3	0.04	<5	4	<10	<5	10	0.07	<5	68	<5	5	52
194	S8R281432	<0.2	2.51	5	42	<1	<5	0.21	<1	22	10	52	5.44	<5	0.04	2	6	1.87	890	<1	0.07	9	510	3	0.06	<5	3	<10	<5	8	0.17	<5	98	<5	2	84
211	S8R281440	<0.2	0.00	00	040	<1	<5	0.14	<1	10	40	24	2.24	<5	0.06	22	14	0.69	380	<1	0.07	28	250	15	<0.01	<5	6	<10	<5	12	0.08	<5	70	<5	11	78

Standard:

Pb129a	11.2	0.83	5	62	<1	<5	0.49	54	5	10	1426	1.59	<5	0.10	4	<2	0.71	370	2	0.05	5	400	6120	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	3	9986
Pb129a	11.2	0.86	5	62	<1	<5	0.49	54	5	10	1418	1.59	<5	0.10	4	<2	0.66	370	2	0.05	5	400	6132	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	3	>10000
Pb129a	11.8	0.84	5	62	<1	<5	0.50	57	5	12	1440	1.58	<5	0.09	4	<2	0.68	365	2	0.05	5	410	6120	0.79	15	<1	<10	<5	30	0.04	<5	18	<5	2	>10000
Pb129a	11.0	0.86	5	66	<1	<5	0.45	58	5	12	1402	1.60	<5	0.12	4	<2	0.68	360	2	0.05	5	410	6324	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	2	>10000
Pb129a	11.4	0.83	5	66	<1	<5	0.48	58	5	12	1414	1.62	<5	0.10	4	2	0.68	380	2	0.05	5	410	6327	0.80	15	1	<10	<5	30	0.04	<5	18	<5	3	>10000
Pb129a	11.2	0.85	5	68	<1	<5	0.48	57	5	10	1394	1.55	<5	0.09	4	<2	0.66	370	2	0.05	5	410	6096	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	3	9984
Pb129a	11.8	0.83	<5	62	<1	<5	0.50	55	5	10	1394	1.50	<5	0.10	4	<2	0.65	365	2	0.05	5	400	6246	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	2	9988
Pb129a	11.2	0.82	<5	66	<1	<5	0.50	56	5	10	1412	1.59	<5	0.10	4	<2	0.69	385	2	0.05	5	410	6210	0.80	15	1	<10	<5	30	0.04	<5	18	<5	3	>10000
Pb129a	11.4	0.86	5	66	<1	<5	0.44	59	5	12	1398	1.57	<5	0.11	4	<2	0.68	370	2	0.05	5	420	6261	0.80	15	<1	<10	<5	30	0.04	<5	18	<5	3	>10000
Till3	1.4	1.00	75	38	<1	<5	0.45	<1	11	64	20	1.90	<5	0.06	14	16	0.57	310	<1	0.07	30	460	18	0.08	<5	3	<10	<5	16	0.05	<5	36	<5	5	40

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
TiI3		1.4	1.07	75	36	<1	<5	0.53	<1	11	62	20	2.07	<5	0.06	12	14	0.57	305	<1	0.08	29	460	18	0.08	<5	3	<10	<5	16	0.05	<5	36	<5	5	40
TiI3		1.4	1.05	70	32	<1	<5	0.49	<1	11	60	20	2.00	<5	0.06	12	14	0.54	310	<1	0.08	27	460	21	0.08	<5	3	<10	<5	18	0.06	<5	38	<5	5	40
TiI3		1.4	0.99	75	34	<1	<5	0.49	<1	12	60	20	1.93	<5	0.07	14	12	0.54	315	<1	0.08	28	460	18	0.08	<5	3	<10	<5	18	0.06	<5	36	<5	6	40
TiI3		1.6	0.99	75	32	<1	<5	0.48	<1	12	60	20	1.92	<5	0.08	12	14	0.56	300	<1	0.08	28	460	18	0.08	<5	3	<10	<5	18	0.06	<5	36	<5	5	42
TiI3		1.6	1.00	75	34	<1	<5	0.50	<1	12	62	22	1.94	<5	0.08	14	16	0.59	310	<1	0.08	30	470	18	0.09	<5	3	<10	<5	18	0.06	<5	38	<5	5	42
TiI3		1.4	0.97	70	32	<1	<5	0.51	<1	12	60	20	2.06	<5	0.08	12	16	0.54	315	<1	0.08	28	460	21	0.08	<5	3	<10	<5	18	0.06	<5	38	<5	5	40

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/sa/el

dt/msr_8168AS/msr8168BS/msr8168CS/msr8168DS/msr8168ES

XLS/11



ECO TECH LABORATORY LTD.

Norman Monteith

B.C. Certified Assayer

PDFill PDF Editor with Free Writer and Tools



CERTIFICATE OF ANALYSIS AW 2011-8191

Kestrel Gold Corp.
 #8-46225 Rancho Drive
Chilliwack, BC
 V4Z 0A5
 Attn: Kevin Nephin

30-Sep-11

No. of samples received: 198

Sample Type: Soil

Project: Dawson Area

Shipment #: 7

Submitted by: All Terrane Mineral Exploration

ET #.	Tag #	Au (ppb)
1	S8R280198	10
2	S8R280199	<5
3	S8R280200	<5
4	S8R280201	<5
5	S8R280202	5
6	S8R280203	<5
7	S8R280204	<5
8	S8R280205	5
9	S8R280206	<5
10	S8R280207	15
11	S8R280208	5
12	S8R280209	50
13	S8R280210	10
14	S8R280211	25
15	S8R280212	10
16	S8R280213	<5
17	S8R280214	10
18	S8R280215	<5
19	S8R280216	10
20	S8R280217	5
21	S8R280218	10
22	S8R280219	10
23	S8R280220	55
24	S8R280221	20
25	S8R280222	35
26	S8R280223	30
27	S8R280224	<5
28	S8R280225	10
29	S8R280226	5

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8191

30-Sep-11

ET #.	Tag #	Au (ppb)
42	S8R281615	5
43	S8R281616	5
44	S8R281617	<5
45	S8R281618	5
46	S8R281619	20
47	S8R281620	<5
48	S8R281621	<5
49	S8R281622	<5
50	S8R281623	<5
51	S8R281624	<5
52	S8R281625	5
53	S8R281626	5
54	S8R281627	5
55	S8R281628	5

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8191

30-Sep-11

ET #.	Tag #	Au (ppb)

PDFill PDF Editor with Free Writer and Tools



30-Sep-11

PDFFill PDF Editor with Free Writer and Tools

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8191

30-Sep-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

QC DATA:

Repeat:

1	S8R280198	10
10	S8R280207	20
19	S8R280216	15

Eco Tech Laboratory Ltd.
 10041 Dallas Drive
 Kamloops, BC
 V2C 6T4 Canada
 Tel + 250 573 5700
 Fax + 250 573 4557
 Toll Free + 1 877 573 5755
 www.stewartgroupglobal.com



StewartGroup
 Geochemical & Assay

Kestrel Gold Corp. AW11-8191

30-Sep-11

ET #.	Tag #	Au (ppb)
45	S8R281618	10
54	S8R281627	5

PDFfill PDF Editor with Free Writer and Tools

Standard:

OXE86	590
OXE86	620
OXE86	620
OXE86	600
OXE86	610
OXE86	610

FA Geochem/AA Finish

NM/EL
 XLS/11

ECO TECH LABORATORY LTD.
 Norman Monteith
 B.C. Certified Assayer

Stewart Group
ECO TECH LABORATORY LTD.
 10041 Dallas Drive
KAMLOOPS, B.C.
 V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8191

Kestrel Gold Corp.
 #8-46225 Ranchero Drive
Chilliwack, BC
 V4Z 0A5
 Attn: Kevin Nephin

Phone: 250-573-5700
 Fax : 250-573-4557

No. of samples received: 198

Sample Type: Soil

Project: Dawson Area**Shipment #: 7**

Submitted by: All Terrane Mineral Exploration

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S8R280198	<0.2	1.91	<5	52	<1	<5	0.16	<1	15	254	46	2.31	<5	0.02	4	10	2.09	440	1	0.02	91	350	12	<0.01	<5	3	<10	<5	8	0.09	<5	56	<5	3	42
2	S8R280199	<0.2	1.91	5	76	<1	<5	0.18	<1	15	16	40	2.99	<5	0.03	6	10	1.44	505	1	0.03	13	470	12	<0.01	<5	2	<10	<5	10	0.07	<5	60	<5	3	62
3	S8R280200	<0.2	1.70	<5	72	<1	<5	0.13	<1	11	16	36	2.64	<5	0.02	6	10	1.11	410	2	0.03	11	670	15	<0.01	<5	1	<10	<5	8	0.02	<5	66	<5	3	74
4	S8R280201	<0.2	1.89	10	104	<1	<5	0.13	<1	13	26	42	2.42	<5	0.04	10	12	0.84	455	2	0.03	17	410	24	<0.01	<5	4	<10	<5	10	0.06	<5	56	<5	4	110
5	S8R280202	<0.2	1.89	15	60	<1	5	0.12	<1	17	20	126	2.58	<5	0.03	6	14	1.32	890	2	0.03	15	540	33	<0.01	<5	4	<10	<5	10	0.08	<5	66	<5	3	396
6	S8R280203	<0.2	1.86	5	80	<1	<5	0.10	<1	14	40	32	2.92	<5	0.04	6	12	1.46	505	2	0.03	19	430	15	<0.01	<5	3	<10	<5	8	0.05	<5	66	<5	3	50
7	S8R280204	<0.2	2.12	15	186	<1	<5	0.19	<1	17	64	78	3.17	<5	0.04	12	14	1.43	530	2	0.03	31	500	18	<0.01	<5	5	<10	<5	12	0.03	<5	78	<5	5	74
8	S8R280205	<0.2	1.78	20	132	<1	<5	0.12	<1	13	32	42	3.10	<5	0.04	10	14	0.85	435	2	0.03	20	440	21	<0.01	<5	3	<10	<5	10	0.04	<5	68	<5	3	82
9	S8R280206	<0.2	2.65	10	90	<1	5	0.17	<1	32	10	166	5.26	<5	0.13	12	10	1.86	985	2	0.04	12	230	15	<0.01	<5	4	<10	<5	8	0.17	<5	112	<5	2	86
10	S8R280207	0.4	1.63	35	146	<1	5	0.13	<1	16	22	170	4.07	<5	0.04	10	14	0.85	590	2	0.03	18	330	27	<0.01	<5	9	<10	<5	8	0.02	<5	86	<5	7	294
11	S8R280208	<0.2	1.91	10	92	<1	<5	0.13	<1	16	20	68	3.52	<5	0.03	8	14	1.13	455	1	0.03	16	400	18	<0.01	<5	4	<10	<5	10	0.03	<5	78	<5	3	76
12	S8R280209	0.6	1.88	60	208	<1	<5	0.82	<1	15	22	40	2.53	<5	0.05	8	20	1.24	625	1	0.03	19	570	39	0.03	<5	6	<10	<5	40	0.04	<5	62	<5	7	82
13	S8R280210	0.4	1.70	80	188	<1	<5	0.03	<1	10	20	72	2.71	<5	0.03	10	22	1.01	500	2	0.03	17	500	17	<0.01	<5	10	<10	<5	10	0.03	<5	98	<5	7	112
14	S8R280211	0.4	1.70	80	188	<1	<5	0.03	<1	10	20	72	2.71	<5	0.03	10	22	1.01	500	2	0.03	17	500	17	<0.01	<5	10	<10	<5	10	0.03	<5	98	<5	7	112
15	S8R280212	<0.2	2.56	5	92	<1	5	0.22	<1	30	244	106	4.13	<5	0.03	8	16	3.15	895	2	0.04	106	610	18	<0.01	<5	10	<10	<5	10	0.03	<5	98	<5	7	112
16	S8R280213	<0.2	1.64	10	138	<1	<5	0.49	<1	17	60	34	2.36	<5	0.03	6	10	1.22	685	1	0.03	33	540	12	0.02	<5	4	<10	<5	20	0.03	<5	54	<5	4	78
17	S8R280214	<0.2	1.88	5	112	<1	<5	0.46	<1	18	54	32	2.90	<5	0.03	6	10	1.53	675	1	0.03	30	710	12	0.01	<5	5	<10	<5	18	0.03	<5	66	<5	4	84
18	S8R280215	<0.2	1.47	<5	88	<1	<5	0.35	<1	13	64	22	2.03	<5	0.02	6	8	1.22	480	1	0.02	32	500	9	0.01	<5	4	<10	<5	14	0.03	<5	54	<5	3	92
19	S8R280216	<0.2	1.77	5	98	<1	<5	0.45	<1	16	104	34	2.39	<5	0.02	6	10	1.64	545	1	0.03	48	770	12	0.01	<5	6	<10	<5	18	0.03	<5	66	<5	4	96
20	S8R280217	<0.2	1.93	5	164	<1	<5	0.82	<1	21	148	60	2.90	<5	0.03	6	12	2.01	740	1	0.03	66	600	15	0.04	<5	9	<10	<5	28	0.02	<5	84	<5	6	140
21	S8R280218	0.2	2.03	5	168	<1	5	0.99	<1	27	182	110	3.46	<5	0.03	6	14	2.10	1070	1	0.03	88	730	15	0.04	<5	12	<10	<5	30	0.02	<5	94	<5	9	120
22	S8R280219	0.4	2.02	5	154	<1	5	0.82	<1	26	188	120	3.72	<5	0.03	8	14	2.40	795	2	0.03	86	550	15	0.01	<5	11	<10	<5	14	0.03	<5	88	<5	8	130

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
41	S8R281615	<0.2	1.25	<5	152	<1	<5	0.52	<1	20	308	82	2.54	<5	0.03	16	12	2.36	760	1	0.03	104	830	42	0.02	<5	4	<10	<5	16	0.02	<5	56	<5	12	160
42	S8R281615	<0.2	2.15	<5	152	<1	<5	0.52	<1	20	308	82	2.54	<5	0.03	16	12	2.36	760	1	0.03	104	830	42	0.02	<5	4	<10	<5	16	0.02	<5	56	<5	12	160
43	S8R281616	<0.2	1.66	<5	34	<1	<5	0.21	<1	21	366	52	1.87	<5	0.01	<2	10	2.23	380	<1	0.02	140	230	12	<0.01	5	2	<10	<5	4	0.11	<5	38	<5	4	34
44	S8R281617	<0.2	2.23	10	86	<1	5	0.17	<1	19	18	62	3.59	<5	0.03	4	12	1.85	670	1	0.03	17	430	15	<0.01	<5	4	<10	<5	10	0.04	<5	78	<5	3	62
45	S8R281618	<0.2	1.67	10	102	<1	<5	0.10	<1	22	24	2.67	<5	0.03	8	14	0.90	580	2	0.03	12	350	18	<0.01	<5	3	<10	<5	10	0.05	<5	72	<5	3	50	
46	S8R281619	<0.2	2.11	5	108	<1	<5	0.17	<1	19	20	70	3.52	<5	0.03	8	12	1.52	655	1	0.03	18	550	15	<0.01	<5	5	<10	<5	10	0.03	<5	78	<5	6	64
47	S8R281620	<0.2	1.98	10	84	<1	<5	0.14	<1	20	22	14	3.43	<5	0.02	8	10	1.46	800	1	0.03	20	380	21	<0.01	<5	8	<10	<5	8	0.04	<5	66	<5	5	86
48	S8R281621	<0.2	2.23	5	82	<1	5	0.13	<1	23	26	60	3.99	<5	0.03	8	12	1.80	875	1	0.03	23	390	18	<0.01	<5	7	<10	<5	10	0.04	<5	78	<5	5	82
49	S8R281622	<0.2	2.64	5	96	<1	5	0.14	<1	25	30	44	4.32	<5	0.03	6	12	1.70	3815	2	0.04	23	820	33	0.03	<5	7	<10	<5	8	0.03	<5	80	<5	6	62
50	S8R281623	<0.2	1.87	5	70	<1	<5	0.10	<1	16	26	36	3.23	<5	0.05	4	10	1.59	770	1	0.03	17	600	15	<0.01	<5	4	<10	<5	4	0.01	<5	54	<5	4	72
51	S8R281624	<0.2	2.13	10	86	<1	5	0.29	2	21	14	68	4.37	<5	0.04	6	8	1.51	910	2	0.04	12	720	18	0.02	<5	5	<10	<5	12	0.03	<5	106	<5	4	336
52	S8R281625	<0.2	1.94	15	98	<1	<5	0.23	<1	20	22	142	3.78	<5	0.03	8	10	1.25	715	2	0.04	18	570	18	<0.01	<5	6	<10	<5	12	0.04	<5	90	<5	5	294
53	S8R281626	<0.2	2.56	5	144	<1	5	0.32	<1	31	168	130	4.34	<5	0.02	4	12	2.73	2705	1	0.04	71	460	15	<0.01	<5	9	<10	<5	10	0.04	<5	110	<5	6	106
54	S8R281627	<0.2	2.08	10	132	<1	<5	0.40	<1	20	58	102	3.36	<5	0.03	8	12	1.6	730	1	0.03	32	570	18	0.01	<5	6	<10	<5	16	0.05	<5	78	<5	6	186
55	S8R281628	<0.2	1.82	10	366	<1	5	1.10	3	38	40	106	3.45	<5	0.03	6	10	1.24	8980	2	0.04	31	840	18	0.06	<5	5	<10	<5	30	0.03	<5	60	<5	7	164

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
51	00500101	0.01	1.73	1.15	0.03	1	5	0.07	1	15	0.0	54	0.00	5	0.07	10	10	0.04	500	0	0.04	0.5	0.00	0.0	0.04	5	0	10	5	0.0	0.00	5	0.1	5	5	0.1

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
-------	-------	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	----	----	-----	----	----	-----	----	---	----	----	----	----	----	----	----	-----	---	---	---	---	----

QC DATA:**Repeat:**

1	S8R280198	<0.2	1.89	<5	54	<1	<5	0.16	<1	19	252	46	2.37	<5	0.02	4	10	2.17	440	1	0.02	90	360	12	<0.01	<5	3	<10	<5	8	0.08	<5	56	<5	3	42
10	S8R280207	0.4	1.63	35	146	<1	5	0.13	<1	16	22	174	4.13	<5	0.04	10	10	0.87	600	2	0.03	18	330	27	<0.01	<5	9	<10	<5	8	0.02	<5	88	<5	7	296
19	S8R280216	<0.2	1.77	5	96	<1	<5	0.46	<1	16	104	32	2.40	<5	0.02	6	10	1.59	555	1	0.03	48	800	12	0.01	<5	6	<10	<5	16	0.03	<5	66	<5	4	96
30	S8R280230	<0.2	0.90	<5	80	<1	<5	0.07	<1	2	2	8	0.00	<5	0.21	10	2	0.20	100	<1	0.02	8	300	12	<0.01	<5	2	<10	<5	8	0.04	<5	70	<5	11	30
45	S8R281618	<0.2	1.69	10	102	<1	<5	0.10	<1	14	42	26	2.78	<5	0.03	8	14	0.92	610	2	0.03	12	340	15	<0.01	<5	3	<10	<5	10	0.05	<5	72	<5	3	50
54	S8R281627	0.2	2.03	10	132	<1	<5	0.40	<1	20	58	109	3.36	<5	0.03	8	12	1.44	725	2	0.04	32	570	15	0.01	<5	6	<10	<5	16	0.05	<5	76	<5	6	186

Standard:


TILL3	1.4	1.10	85	40	<1	<5	0.57	<1	12	62	22	1.98	<5	0.08	16	18	0.58	315	1	0.04	32	470	21	0.06	<5	4	<10	<5	18	0.06	<5	38	<5	7	44
TILL3	1.4	1.07	80	38	<1	<5	0.55	<1	12	62	22	1.98	<5	0.09	16	18	0.58	310	1	0.04	32	450	21	0.06	<5	4	<10	<5	18	0.06	<5	38	<5	7	44
TILL3	1.2	1.08	85	40	<1	<5	0.57	<1	12	62	22	1.95	<5	0.08	16	18	0.60	320	1	0.04	32	450	21	0.06	<5	4	<10	<5	18	0.06	<5	38	<5	7	44
TILL3	1.4	1.08	85	40	<1	<5	0.55	<1	12	62	22	1.92	<5	0.09	14	18	0.60	310	1	0.04	32	450	21	0.06	<5	4	<10	<5	18	0.06	<5	38	<5	7	40
TILL3	1.4	1.10	80	38	<1	<5	0.56	<1	12	62	22	1.95	<5	0.09	14	18	0.57	320	1	0.04	32	440	18	0.06	<5	3	<10	<5	18	0.06	<5	38	<5	7	44
TILL3	1.4	1.10	80	38	<1	<5	0.58	<1	13	62	22	1.91	<5	0.09	14	18	0.57	320	1	0.04	32	460	18	0.06	<5	3	<10	<5	18	0.06	<5	38	<5	7	42

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/EL

dl/2_8191AS/2_8191BS

XLS/11



ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer



CERTIFICATE OF ANALYSIS AW 2011-8200

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

14-Oct-11

No. of samples received: 196

Sample Type: Soil

Project: Dawson Area

Shipment #: 7

Submitted by: All Terrane Mineral Expl

ET #.	Tag #	Au (ppb)
1	S8R279683	5
2	S8R279684	5
3	S8R279685	5
4	S8R279686	<5
5	S8R279687	5

PDFill PDF Editor with Free Writer and Tools



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8200

14-Oct-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFfill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8200

14-Oct-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8200

14-Oct-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

Eco Tech Laboratory Ltd.
10041 Dallas Drive
Kamloops, BC
V2C 6T4 Canada
Tel + 250 573 5700
Fax + 250 573 4557
Toll Free + 1 877 573 5755
www.stewartgroupglobal.com



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8200

14-Oct-11

ET #.	Tag #	Au (ppb)
-------	-------	-------------

PDFill PDF Editor with Free Writer and Tools

QC DATA:

Repeat:

1	S8R279683	5
{		
1		
1		
1		



StewartGroup
Geochemical & Assay

Kestrel Gold Corp. AW11-8200

14-Oct-11

[illegible]

Standard:

OXE86	620
OXE86	610
OXE86	605
OXG84	920
OXE86	600
OXG84	920

FA Geochem/AA Finish

NM/cr/el
XLS/11


ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer

14-Oct-11

Stewart Group
ECO TECH LABORATORY LTD.
10041 Dallas Drive
KAMLOOPS, B.C.
V2C 6T4
www.stewartgroupglobal.com

ICP CERTIFICATE OF ANALYSIS AW 2011-8200

Kestrel Gold Corp.
#8-46225 Ranchero Drive
Chilliwack, BC
V4Z 0A5
Attn: Kevin Nephin

Phone: 250-573-5700
Fax : 250-573-4557

No. of samples received: 196
Sample Type: Soil
Project: Dawson Area
Shipment #: 7
Submitted by: All Terrane Mineral Expl

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
1	S8R279683	0.2	1.47	10	174	<1	<5	0.80	<1	17	26	52	2.42	<5	0.03	4	8	0.87	1105	<1	0.02	21	570	18	0.04	<5	3	<10	<5	24	0.01	<5	48	<5	4	86
2	S8R279684	0.2	1.44	10	166	<1	<5	0.70	1	15	36	52	1.99	<5	0.03	6	8	0.79	555	1	0.02	22	540	21	0.04	<5	3	<10	<5	22	0.02	<5	44	<5	4	134
3	S8R279685	0.4	1.69	10	246	<1	<5	0.63	<1	23	48	56	2.61	<5	0.02	6	8	1.00	3375	1	0.02	29	620	21	0.03	<5	3	<10	<5	22	0.02	<5	50	<5	4	128
4	S8R279686	0.6	1.77	15	146	<1	<5	0.63	<1	25	36	100	3.20	<5	0.02	6	8	1.12	980	1	0.02	24	560	24	0.03	<5	5	<10	<5	20	0.02	<5	62	<5	6	154
5	S8R279687	0.4	1.70	10	174	<1	<5	0.77	<1	15	38	68	2.80	<5	0.02	6	8	0.93	925	<1	0.02	20	560	24	0.04	<5	4	<10	<5	24	0.02	<5	54	<5	5	170

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
91	S8D270712	1.0	1.36	1.75	0.00	1	5	0.04	1	10	0.0	10	0.00	5	0.01	0	15	1.13	0.15	0	0.00	15	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
74	000000000	0.0	1.07	5	1.10	1	5	0.10	1	10	0.0	10	0.05	0.005	0.005	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0	0.0

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
444	08D0370300	0.0	1.87	5	150	1	5	0.14	1	10	14	00	0.14	5	0.00	0.1	0	0.74	100	1	0.00	10	000	10	0.04	5	1	10	5	10	0.10	5	00	5	0	70

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
151	88D270922	0.0	1.50	5	0.00	1	5	0.70	1	11	0.0	10	0.04	5	0.05	10	10	0.05	0.00	1	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00

PDFfill PDF Editor with Free Writer and Tools

Et #.	Tag #	Ag	Al%	As	Ba	Be	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	Hg	K%	La	Li	Mg%	Mn	Mo	Na%	Ni	P	Pb	S%	Sb	Sc	Se	Sn	Sr	Ti%	U	V	W	Y	Zn
101	S8R279683	<0.2	1.67	10	168	<1	<5	0.76	<1	17	26	52	2.42	<5	0.03	4	8	0.88	1065	1	0.02	18	560	15	0.04	<5	3	<10	<5	24	0.01	<5	48	<5	6	58

QC DATA:

Repeat:																																				
1	S8R279683	<0.2	1.45	10	168	<1	<5	0.76	<1	17	26	52	2.42	<5	0.03	4	8	0.88	1065	1	0.02	18	560	15	0.04	<5	3	<10	<5	24	0.01	<5	48	<5	4	84
10	S8R279692	0.8	1.96	140	156	<1	<5	0.28	<1	18	26	58	2.22	<5	0.04	6	10	1.00	505	2	0.03	18	470	22	0.04	<5	4	<10	<5	18	0.01	<5	38	<5	7	40

PDFfill PDF Editor with Free Writer and Tools

Standard:

TILL3	1.4	1.14	85	38	<1	<5	0.57	<1	14	62	22	1.94	<5	0.06	14	16	0.65	305	1	0.03	30	450	21	0.06	<5	3	<10	<5	16	0.06	<5	38	<5	6	38
TILL3	1.4	1.10	85	38	<1	<5	0.58	<1	13	66	22	1.97	<5	0.06	14	16	0.65	310	1	0.03	30	450	18	0.06	<5	3	<10	<5	14	0.05	<5	38	<5	5	38
TILL3	1.4	1.12	85	38	<1	<5	0.56	<1	14	62	22	1.95	<5	0.06	14	16	0.65	300	1	0.03	31	450	21	0.06	<5	3	<10	<5	16	0.05	<5	38	<5	5	40
TILL3	1.4	1.15	85	44	<1	<5	0.55	<1	15	64	22	2.01	<5	0.05	16	16	0.63	315	1	0.04	32	460	21	0.06	<5	4	<10	<5	18	0.06	<5	36	<5	7	42
TILL3	1.4	1.11	85	44	<1	<5	0.54	<1	15	66	22	2.06	<5	0.05	16	16	0.63	315	1	0.04	31	460	21	0.06	<5	4	<10	<5	18	0.06	<5	38	<5	7	42
TILL3	1.4	1.12	90	42	<1	<5	0.54	<1	14	66	22	2.06	<5	0.05	16	16	0.63	315	1	0.04	32	460	21	0.07	<5	4	<10	<5	18	0.06	<5	38	<5	7	40

ICP: Aqua Regia Digest / ICP- AES Finish.

NM/cr/el
dl/2_8200AS/2_8200BS
XLS/11



ECO TECH LABORATORY LTD.
Norman Monteith
B.C. Certified Assayer