



Certificate of Analysis

Work Order: VC121773

To: **Kendra Johnston**
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA STREET
VACOUVER BC V6B 4N8

Date: Aug 22, 2012

P.O. No. : PO#: FL-90103-05/SHIPMENT YK008-FLOW
Project No. : -
No. Of Samples : 74
Date Submitted : Jul 20, 2012
Report Comprises : Pages 1 to 9
(Inclusive of Cover Sheet)

Distribution of unused material:

Active files - upstairs:

Certified By :



Satpaul Gill
QAQC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method
M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion
Methods marked with an asterisk (e.g. *NAA08V) were subcontracted
Methods marked with the @ symbol (e.g. @AAS21E) denote accredited tests

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	WtKg WGH79 0.001 kg	Au FAA313 5 ppb	Ag ICP14B 2 ppm	Al ICP14B 0.01 %	As ICP14B 3 ppm	Be ICP14B 0.5 ppm	Ca ICP14B 0.01 %	Ba ICP14B 5 ppm	Bi ICP14B 5 ppm	Cd ICP14B 1 ppm
L399901	1.014	<5	<2	2.07	28	0.5	1.14	207	<5	<1
L399902	1.028	<5	<2	1.70	25	0.5	1.14	142	<5	<1
L399903	1.364	<5	<2	1.56	33	<0.5	1.12	155	<5	1
L399904	1.132	<5	<2	1.00	10	0.7	0.15	73	<5	<1
L399905	1.098	<5	<2	3.64	11	<0.5	1.11	325	<5	<1
L399906	1.098	9	<2	2.27	24	<0.5	0.81	167	<5	<1
L399907	1.142	<5	<2	1.85	14	<0.5	0.65	226	<5	<1
L399908	1.462	<5	<2	2.19	121	0.6	0.81	161	<5	<1
L399909	1.088	<5	<2	2.27	11	<0.5	0.59	198	<5	1
L399910	1.276	6	<2	4.31	8	<0.5	2.13	103	<5	<1
L399911	1.198	5	<2	4.09	9	1.5	1.40	184	<5	<1
L399912	1.200	<5	<2	0.82	22	<0.5	0.50	76	<5	<1
L399951	1.768	<5	<2	2.93	24	0.8	1.49	66	<5	<1
L399952	1.064	<5	<2	0.42	18	0.7	1.01	49	<5	<1
L399953	1.226	<5	<2	0.36	9	0.9	0.45	31	<5	<1
L399954	1.268	<5	<2	1.15	31	<0.5	0.22	40	<5	<1
L399955	0.800	<5	<2	1.08	15	0.7	2.57	62	<5	<1
L399956	1.056	<5	<2	1.88	7	1.3	1.15	79	<5	<1
L399957	1.490	<5	<2	1.27	35	0.7	1.25	45	<5	<1
L399958	0.902	<5	<2	1.09	15	0.6	0.52	32	<5	<1
L399959	1.364	<5	<2	0.41	18	0.5	0.14	17	<5	<1
L399960	1.004	<5	<2	3.67	20	<0.5	2.34	98	<5	<1
L399961	1.176	<5	<2	1.77	16	0.5	0.98	132	<5	<1
L399962	1.468	<5	<2	1.34	12	<0.5	0.53	166	<5	<1
L399963	1.442	6	<2	1.52	5	<0.5	0.26	173	<5	<1
L399964	1.260	<5	<2	2.69	32	0.6	1.48	182	<5	<1
L399965	1.200	<5	<2	2.73	10	0.8	0.99	207	<5	<1
L399966	1.435	<5	<2	3.29	13	<0.5	1.53	101	<5	<1
L399967	1.020	<5	<2	2.98	4	0.6	0.86	235	<5	<1
L399968	0.975	<5	<2	0.55	11	0.8	0.17	66	<5	<1
L399969	1.165	<5	<2	0.79	15	<0.5	0.22	169	<5	<1
L399970	0.975	<5	<2	1.35	8	0.8	0.36	107	<5	<1
L399971	1.275	<5	<2	1.91	15	1.0	0.93	209	<5	<1
L399972	1.135	<5	<2	3.30	27	1.3	2.59	135	<5	<1
L399973	1.065	<5	<2	3.96	121	1.0	1.65	139	<5	<1
L399974	1.300	<5	<2	0.79	9	0.7	0.39	50	<5	<1
L399975	1.210	<5	<2	0.50	19	0.6	0.08	24	<5	<1
L399976	1.220	<5	<2	0.50	4	0.7	0.27	21	<5	<1
L399977	1.440	<5	<2	1.14	8	<0.5	0.90	37	<5	<1
L399978	1.380	<5	<2	0.76	4	<0.5	0.76	61	<5	<1
L399979	1.840	<5	<2	0.42	6	<0.5	0.61	46	<5	<1
L399980	1.435	<5	<2	1.13	3	<0.5	1.02	58	6	<1
L399981	1.410	<5	<2	1.87	10	<0.5	1.24	96	6	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	WtKg WGH79 0.001 kg	Au FAA313 5 ppb	Ag ICP14B 2 ppm	Al ICP14B 0.01 %	As ICP14B 3 ppm	Be ICP14B 0.5 ppm	Ca ICP14B 0.01 %	Ba ICP14B 5 ppm	Bi ICP14B 5 ppm	Cd ICP14B 1 ppm
L399982	1.395	<5	<2	2.31	15	<0.5	1.42	106	<5	<1
L399983	1.195	<5	<2	2.21	<3	<0.5	0.79	223	<5	<1
L399984	1.185	<5	<2	2.17	14	<0.5	1.51	169	8	<1
L399985	1.200	<5	<2	1.94	20	<0.5	1.22	130	7	<1
L399986	1.130	<5	<2	6.28	7	<0.5	2.93	414	<5	<1
L399987	1.325	<5	<2	2.62	17	<0.5	1.51	132	<5	<1
L399988	1.250	<5	<2	2.03	26	<0.5	1.00	154	<5	<1
L399989	1.315	<5	<2	1.58	11	<0.5	0.77	99	<5	<1
L399990	1.310	<5	<2	3.27	19	<0.5	1.93	197	<5	<1
L399991	1.395	<5	<2	1.36	4	<0.5	0.21	144	<5	<1
L399993	1.400	<5	<2	2.01	45	<0.5	2.24	105	<5	<1
L399994	1.530	<5	<2	3.06	21	<0.5	1.97	103	<5	<1
L399995	1.610	<5	<2	1.15	16	<0.5	0.78	52	<5	<1
L399996	1.510	<5	<2	0.39	8	<0.5	0.20	26	6	<1
L399997	1.375	<5	<2	1.30	11	<0.5	0.67	53	<5	<1
L399998	1.485	<5	<2	0.38	<3	0.7	0.38	53	<5	<1
L399999	1.585	<5	<2	0.76	5	<0.5	0.67	46	<5	<1
L400000	0.365	<5	<2	0.07	<3	<0.5	>15.0	19	<5	<1
L401151	0.610	<5	<2	3.26	16	<0.5	2.56	130	<5	<1
L401152	0.715	20	<2	2.20	29	0.5	0.97	190	<5	<1
L401153	0.980	<5	<2	2.69	12	<0.5	1.92	233	<5	<1
L401154	1.135	<5	<2	3.20	5	<0.5	1.98	196	<5	<1
L401155	1.090	<5	<2	0.35	8	0.5	0.16	33	<5	<1
L401156	1.395	<5	<2	0.37	10	<0.5	0.15	11	<5	<1
L401157	0.305	<5	<2	2.05	6	0.8	1.04	64	<5	<1
L401159	1.045	<5	<2	1.03	24	<0.5	0.85	44	7	<1
L401209	0.575	<5	<2	0.58	<3	<0.5	0.22	39	<5	<1
L401210	0.915	<5	<2	0.47	8	0.7	0.17	26	<5	<1
L401211	0.690	<5	<2	0.28	5	0.7	0.05	23	<5	<1
L401213	0.670	<5	<2	0.46	11	0.8	0.09	40	<5	<1
L401215	0.875	<5	<2	0.85	<3	<0.5	0.75	56	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L399901	9	31	10.0	3.64	<1	0.76	12.0	32	1.01	436
L399902	9	44	28.3	3.68	<1	0.44	12.0	33	0.93	434
L399903	8	40	20.2	4.09	<1	0.49	10.7	30	0.93	415
L399904	4	12	9.1	1.53	<1	0.34	39.0	18	0.46	255
L399905	11	113	60.5	3.57	<1	1.07	4.4	46	1.31	329
L399906	10	50	42.0	2.88	<1	0.37	5.3	29	1.09	533
L399907	8	22	39.7	2.23	<1	0.33	6.1	16	0.67	343
L399908	6	17	40.3	2.21	<1	0.43	15.3	16	0.67	351
L399909	16	16	33.8	4.14	<1	0.41	2.4	35	1.18	443
L399910	12	11	43.5	3.28	<1	0.45	3.4	37	1.13	316
L399911	15	135	69.6	3.55	<1	1.62	9.5	49	1.94	302
L399912	4	22	31.8	2.75	<1	0.24	22.6	13	0.41	218
L399951	13	70	19.2	2.96	<1	0.76	16.8	25	1.02	248
L399952	1	5	1.5	0.59	<1	0.33	31.9	2	0.02	263
L399953	<1	4	2.2	0.71	<1	0.43	61.8	5	0.02	222
L399954	6	16	27.2	2.34	<1	0.34	27.7	21	0.67	228
L399955	2	16	3.7	1.54	<1	0.10	7.6	11	0.61	498
L399956	8	28	2.2	2.22	<1	0.66	14.8	22	0.97	316
L399957	8	18	6.9	1.85	<1	0.21	7.4	12	0.56	262
L399958	7	12	12.0	2.17	<1	0.13	20.2	12	0.58	299
L399959	3	7	24.9	1.02	<1	0.13	18.5	4	0.10	109
L399960	12	230	21.8	3.37	<1	0.39	7.9	16	0.76	347
L399961	10	52	25.7	2.90	<1	0.33	13.7	26	0.84	334
L399962	8	47	19.1	3.20	<1	0.39	18.1	19	0.96	302
L399963	6	7	6.6	2.47	<1	0.30	12.4	23	1.07	415
L399964	7	19	3.2	3.39	<1	0.96	14.8	37	1.03	468
L399965	8	147	10.0	3.47	<1	0.98	26.4	34	2.16	551
L399966	20	5	3.3	3.95	<1	0.55	4.9	24	1.87	437
L399967	6	24	14.0	3.36	<1	1.08	22.6	26	1.83	421
L399968	2	6	3.1	0.88	<1	0.30	51.1	6	0.09	181
L399969	3	6	3.4	1.05	<1	0.23	21.8	10	0.20	276
L399970	2	4	19.0	1.16	<1	0.46	10.0	10	0.49	121
L399971	6	30	14.6	3.42	<1	0.54	32.9	26	1.07	328
L399972	7	89	6.6	3.70	<1	0.57	28.3	27	1.33	483
L399973	14	119	5.5	3.56	<1	1.15	26.1	48	1.56	418
L399974	3	12	1.5	1.23	<1	0.21	39.5	9	0.23	258
L399975	3	5	5.8	1.24	<1	0.23	39.1	4	0.06	205
L399976	1	9	3.5	1.14	<1	0.15	34.6	7	0.14	199
L399977	4	41	6.2	1.50	1	0.44	5.2	13	0.53	215
L399978	4	24	11.4	0.75	<1	0.27	4.6	6	0.35	117
L399979	7	9	46.6	1.14	<1	0.09	23.6	3	0.21	135
L399980	5	24	2.3	1.37	1	0.32	10.8	12	0.59	232
L399981	13	26	15.4	4.00	1	0.43	17.7	30	0.86	412

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L399982	10	38	9.8	4.51	<1	0.74	15.1	33	1.17	443
L399983	4	6	31.5	3.05	1	0.49	13.3	34	1.39	592
L399984	7	34	9.9	3.87	<1	0.65	14.3	27	1.05	428
L399985	10	47	51.0	3.71	2	0.51	17.1	32	0.99	369
L399986	19	142	74.7	5.84	<1	1.58	11.0	37	2.65	545
L399987	10	20	10.0	4.32	<1	0.95	15.4	49	1.35	510
L399988	18	61	45.1	3.97	<1	0.47	24.1	24	1.23	645
L399989	6	44	14.4	2.21	<1	0.43	29.7	13	0.67	276
L399990	16	40	6.9	5.13	<1	1.32	14.2	39	2.04	1110
L399991	3	5	3.2	1.51	<1	0.61	8.0	13	0.57	151
L399993	15	13	<0.5	4.56	<1	0.24	11.2	15	1.36	501
L399994	3	66	2.0	5.75	<1	0.48	20.9	30	1.41	468
L399995	6	7	7.5	1.46	<1	0.20	23.6	10	0.35	272
L399996	2	6	3.0	1.17	1	0.16	28.0	4	0.08	172
L399997	3	42	3.2	1.70	<1	0.16	20.2	13	0.58	269
L399998	1	5	9.8	1.08	<1	0.17	30.1	3	0.09	240
L399999	5	11	34.7	1.31	<1	0.16	14.3	7	0.47	172
L400000	<1	1	<0.5	0.45	<1	0.05	2.8	<1	12.5	194
L401151	9	40	22.2	5.77	<1	0.65	13.0	50	2.29	917
L401152	13	25	6.3	3.45	<1	0.51	19.1	35	0.99	694
L401153	9	30	10.0	5.19	<1	0.94	21.8	41	1.96	873
L401154	11	44	24.3	6.04	<1	1.10	12.4	40	2.48	1100
L401155	<1	5	2.2	0.92	<1	0.23	36.5	3	0.04	150
L401156	<1	5	4.6	1.16	<1	0.22	31.2	5	0.04	138
L401157	3	21	2.6	2.00	2	0.34	21.6	20	0.63	254
L401159	7	34	60.7	3.42	2	0.19	14.3	9	0.48	253
L401209	1	7	9.4	1.47	<1	0.17	23.9	10	0.19	210
L401210	<1	5	2.8	0.99	<1	0.28	27.9	4	0.03	95
L401211	1	5	5.6	0.80	<1	0.21	27.0	3	0.02	92
L401213	2	4	8.7	0.88	<1	0.32	25.3	4	0.07	87
L401215	5	14	21.7	1.29	<1	0.39	13.3	7	0.39	181

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L399901	<1	0.21	8	0.13	13	0.01	<5	4.3	<10	78.2
L399902	1	0.17	9	0.16	11	0.09	<5	7.0	<10	68.1
L399903	<1	0.16	4	0.17	9	0.06	<5	4.5	<10	58.6
L399904	3	0.06	9	0.02	<2	0.08	<5	1.6	<10	5.1
L399905	2	0.16	36	0.02	3	0.50	<5	13.6	<10	35.3
L399906	2	0.15	39	0.04	3	1.02	<5	6.7	<10	37.4
L399907	1	0.13	22	0.03	2	0.53	<5	3.7	<10	22.2
L399908	11	0.16	31	0.04	123	0.10	8	6.5	<10	65.6
L399909	2	0.14	10	0.03	7	1.20	<5	11.9	<10	21.0
L399910	2	0.19	11	0.02	<2	1.15	<5	7.2	<10	108
L399911	<1	0.36	62	0.06	<2	0.59	<5	10.2	<10	51.6
L399912	<1	0.08	8	0.12	33	0.75	<5	2.6	<10	43.0
L399951	1	0.31	35	0.08	9	0.17	<5	7.4	<10	130
L399952	<1	0.05	3	<0.01	<2	<0.01	<5	<0.5	<10	22.4
L399953	<1	0.05	3	<0.01	8	0.01	<5	<0.5	<10	11.1
L399954	3	0.10	10	<0.01	3	0.12	<5	0.5	<10	13.5
L399955	1	0.08	7	0.11	3	<0.01	<5	0.7	<10	46.8
L399956	<1	0.12	11	0.08	3	0.02	<5	4.0	<10	60.0
L399957	<1	0.07	7	0.08	4	0.02	<5	3.4	<10	75.1
L399958	<1	0.08	7	0.07	<2	0.01	<5	3.2	<10	21.4
L399959	4	0.06	3	0.02	<2	<0.01	<5	0.5	<10	14.0
L399960	<1	0.39	53	0.05	3	0.17	<5	4.9	<10	88.0
L399961	<1	0.18	20	0.11	4	0.36	<5	4.5	<10	69.0
L399962	2	0.10	22	0.11	9	0.30	<5	4.9	<10	80.2
L399963	<1	0.07	7	0.03	<2	0.72	<5	4.2	<10	15.7
L399964	2	0.32	4	0.16	<2	0.12	<5	6.1	<10	144
L399965	<1	0.13	48	0.08	<2	0.12	<5	8.5	<10	33.1
L399966	<1	0.24	7	0.05	5	0.23	<5	5.7	<10	67.8
L399967	<1	0.16	9	0.04	<2	0.10	<5	11.4	<10	30.6
L399968	<1	0.04	4	0.02	9	<0.01	<5	0.8	<10	6.1
L399969	<1	0.04	10	0.02	<2	<0.01	<5	0.6	<10	9.6
L399970	2	0.11	3	0.01	2	0.12	<5	3.2	<10	26.4
L399971	3	0.13	11	0.13	5	0.05	<5	5.6	<10	69.0
L399972	<1	0.45	33	0.11	2	0.07	<5	8.8	<10	143
L399973	<1	0.37	51	0.07	3	0.04	<5	12.3	<10	178
L399974	1	0.09	4	0.03	9	<0.01	<5	2.0	<10	30.9
L399975	2	0.06	2	<0.01	6	<0.01	<5	1.0	<10	5.1
L399976	2	0.05	2	0.02	16	<0.01	<5	1.5	<10	12.9
L399977	<1	0.10	19	0.10	2	<0.01	<5	3.3	<10	48.9
L399978	2	0.07	11	0.05	5	<0.01	6	2.0	<10	35.1
L399979	2	0.08	4	0.06	8	0.26	6	1.2	<10	163
L399980	2	0.09	8	0.06	5	<0.01	<5	2.5	<10	81.8
L399981	2	0.20	7	0.13	22	0.61	7	3.7	<10	77.9

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L399982	3	0.28	5	0.17	10	0.19	<5	6.4	<10	109
L399983	2	0.13	4	0.03	8	0.24	<5	5.9	<10	33.1
L399984	2	0.30	5	0.14	10	<0.01	7	5.2	<10	107
L399985	2	0.19	14	0.17	12	0.12	6	5.9	<10	49.3
L399986	1	0.43	54	0.09	12	1.82	8	16.3	<10	86.6
L399987	3	0.26	4	0.18	10	0.12	<5	4.6	<10	117
L399988	3	0.16	29	0.15	30	0.31	8	6.1	<10	44.6
L399989	1	0.17	14	0.05	7	0.13	<5	3.1	<10	45.8
L399990	1	0.20	8	0.13	4	<0.01	7	15.0	<10	95.2
L399991	2	0.10	4	<0.01	6	0.07	<5	5.6	<10	19.2
L399993	<1	0.19	9	0.32	8	0.04	8	8.8	<10	83.1
L399994	1	0.32	15	0.11	12	<0.01	8	9.4	<10	89.7
L399995	1	0.15	4	0.04	25	<0.01	7	2.8	<10	62.5
L399996	2	0.05	2	0.01	22	<0.01	<5	1.0	<10	9.4
L399997	2	0.14	12	0.03	9	<0.01	7	3.9	<10	34.7
L399998	2	0.05	7	0.02	23	0.02	<5	1.0	<10	16.0
L399999	3	0.08	8	0.06	5	<0.01	6	3.5	<10	31.5
L400000	1	0.01	2	0.02	<2	<0.01	<5	<0.5	<10	42.0
L401151	2	0.16	6	0.16	5	<0.01	<5	13.5	<10	104
L401152	1	0.09	9	0.08	9	<0.01	<5	6.4	<10	39.7
L401153	2	0.14	5	0.15	15	<0.01	<5	11.5	<10	77.0
L401154	3	0.14	7	0.15	3	<0.01	<5	16.5	<10	71.2
L401155	2	0.05	1	<0.01	10	0.02	<5	0.6	<10	6.5
L401156	3	0.05	2	<0.01	20	0.03	<5	0.7	<10	5.1
L401157	2	0.25	10	0.03	6	<0.01	<5	3.5	<10	62.0
L401159	3	0.11	9	0.06	9	0.04	<5	5.1	<10	36.4
L401209	1	0.06	3	0.02	14	<0.01	<5	1.2	<10	26.0
L401210	2	0.05	1	<0.01	5	<0.01	<5	<0.5	<10	21.6
L401211	2	0.08	2	0.03	4	<0.01	<5	<0.5	<10	3.8
L401213	2	0.12	4	0.03	7	<0.01	<5	0.5	<10	6.7
L401215	2	0.10	8	0.08	4	<0.01	<5	2.1	<10	32.7

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L399901	0.27	114	<10	7.0	60	5.9
L399902	0.29	138	<10	8.0	45	4.6
L399903	0.31	138	<10	7.2	43	4.2
L399904	0.04	16	<10	7.1	33	5.2
L399905	0.16	84	<10	11.5	39	2.9
L399906	0.10	26	<10	5.4	54	1.6
L399907	0.06	20	<10	5.2	49	2.5
L399908	0.06	29	<10	8.7	190	4.6
L399909	0.15	105	<10	3.2	54	1.4
L399910	0.09	56	<10	4.6	28	2.2
L399911	0.28	72	<10	8.9	38	3.3
L399912	0.15	21	10	7.8	26	10.3
L399951	0.29	72	<10	10.6	24	2.4
L399952	<0.01	<1	<10	20.4	8	5.7
L399953	<0.01	<1	<10	18.4	24	5.0
L399954	0.08	11	<10	19.5	22	3.5
L399955	0.05	13	<10	8.1	25	2.4
L399956	0.26	56	<10	5.7	32	3.3
L399957	0.29	42	<10	5.2	20	3.8
L399958	0.17	38	<10	8.6	18	3.0
L399959	0.02	4	<10	9.3	11	8.8
L399960	0.17	110	10	7.3	29	8.2
L399961	0.22	78	<10	7.1	40	10.3
L399962	0.20	86	<10	7.3	31	17.9
L399963	0.04	16	<10	15.0	38	2.3
L399964	0.30	104	<10	10.7	41	7.5
L399965	0.26	77	<10	10.3	52	4.8
L399966	0.28	112	<10	9.6	54	2.7
L399967	0.20	91	<10	7.6	40	5.0
L399968	0.01	4	<10	8.1	27	4.6
L399969	0.01	4	<10	6.0	21	10.4
L399970	0.02	5	<10	9.3	16	9.0
L399971	0.32	96	<10	14.5	33	8.6
L399972	0.35	94	<10	14.2	36	4.9
L399973	0.38	126	<10	21.1	32	5.2
L399974	0.07	15	<10	8.5	19	4.7
L399975	<0.01	1	<10	14.8	17	3.6
L399976	0.04	10	<10	16.7	18	4.6
L399977	0.17	39	<10	4.2	15	3.1
L399978	0.19	19	<10	3.9	10	5.1
L399979	0.13	30	<10	7.7	12	2.7
L399980	0.17	28	<10	4.1	23	4.9
L399981	0.24	121	<10	8.0	119	9.8

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L399982	0.28	146	<10	8.3	48	5.9
L399983	0.09	50	<10	11.1	67	2.8
L399984	0.27	144	<10	8.3	45	5.8
L399985	0.32	128	<10	9.1	47	7.7
L399986	0.32	156	<10	7.9	64	1.7
L399987	0.25	139	<10	11.3	58	11.7
L399988	0.20	110	<10	9.5	76	32.3
L399989	0.13	55	<10	7.5	32	6.5
L399990	0.25	143	<10	10.1	74	7.3
L399991	0.02	3	<10	11.5	25	1.4
L399993	0.43	143	<10	14.4	34	4.5
L399994	0.35	127	<10	16.2	53	4.4
L399995	0.11	36	<10	8.4	34	4.7
L399996	0.03	4	<10	14.1	17	2.6
L399997	0.13	41	<10	11.2	31	5.3
L399998	<0.01	3	<10	8.4	38	4.8
L399999	0.14	30	<10	5.2	14	4.1
L400000	<0.01	2	<10	1.0	14	<0.5
L401151	0.21	149	<10	9.2	61	6.4
L401152	0.11	72	<10	8.3	70	6.4
L401153	0.25	132	<10	11.4	72	9.8
L401154	0.27	165	<10	8.8	79	7.2
L401155	<0.01	<1	<10	11.7	18	3.8
L401156	0.01	1	<10	9.6	26	4.8
L401157	0.12	29	<10	8.9	32	2.2
L401159	0.22	46	<10	12.5	24	3.5
L401209	0.07	9	<10	10.9	19	5.6
L401210	<0.01	3	<10	4.9	9	4.1
L401211	<0.01	2	<10	5.2	14	5.9
L401213	<0.01	3	<10	5.7	14	7.6
L401215	0.19	22	<10	4.6	17	4.8

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.