



Certificate of Analysis

Work Order: VC121359

To: **Kendra Johnston**
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA STREET
VACOUVER BC V6B 4N8

Date: Aug 08, 2012

P.O. No. : PO#: SOLO-90403-05
Project No. : -
No. Of Samples : 42
Date Submitted : Jul 06, 2012
Report Comprises : Pages 1 to 5
(Inclusive of Cover Sheet)

Distribution of unused material:

Active files - upstairs:

Certified By :



Satpaul Gill
QAQC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method
M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion
Methods marked with an asterisk (e.g. *NAA08V) were subcontracted
Methods marked with the @ symbol (e.g. @AAS21E) denote accredited tests

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121359 Order: PO#: SOLO-90403-05

Page 2 of 5

Element Method Det.Lim. Units	WtKg WGH79 0.001 kg	Au FAA313 5 ppb	Ag ICP14B 2 ppm	Al ICP14B 0.01 %	As ICP14B 3 ppm	Be ICP14B 0.5 ppm	Ca ICP14B 0.01 %	Ba ICP14B 5 ppm	Bi ICP14B 5 ppm	Cd ICP14B 1 ppm
L398251	0.360	<5	<2	2.20	10	0.8	0.29	728	<5	1
L398252	0.275	6	<2	1.48	15	0.6	0.15	708	<5	1
L398253	0.245	<5	<2	0.99	16	<0.5	0.16	325	<5	<1
L398254	0.290	6	<2	1.12	47	0.8	0.10	268	<5	1
L398255	0.375	<5	<2	2.50	21	0.8	0.20	523	<5	<1
L398256	0.360	5	<2	1.67	15	0.7	0.21	323	<5	<1
L398257	0.305	6	<2	1.89	21	1.0	0.17	278	<5	<1
L398258	0.315	6	<2	1.59	19	0.8	0.11	237	<5	<1
L398259	0.355	<5	<2	2.81	27	1.1	0.10	272	<5	1
L398260	0.375	<5	<2	1.76	4	0.8	0.10	231	<5	<1
L398261	0.330	<5	<2	1.98	5	0.9	0.20	350	<5	<1
L398262	0.285	<5	<2	1.54	<3	0.5	0.07	190	<5	<1
L398263	0.260	<5	<2	2.12	12	0.8	0.11	163	<5	1
L398264	0.340	<5	<2	1.78	15	1.0	0.07	116	<5	<1
L398265	0.325	<5	<2	1.18	13	0.8	0.07	161	<5	<1
L398266	0.325	7	<2	1.62	18	1.0	0.14	224	<5	1
L398267	0.345	5	<2	1.08	61	1.1	0.13	301	<5	2
L398268	0.285	<5	<2	1.28	29	0.5	0.22	286	<5	1
L398269	0.310	5	<2	1.90	19	0.6	0.26	301	<5	<1
L398270	0.300	5	<2	1.48	25	0.7	0.11	334	<5	1
L398271	0.270	<5	<2	1.58	28	0.6	0.16	451	<5	<1
L398272	0.235	13	<2	2.98	20	0.9	0.14	397	<5	1
L398273	0.290	<5	<2	2.05	21	1.0	0.11	361	<5	1
L398274	0.270	<5	<2	2.34	19	1.1	0.19	898	<5	<1
L398275	0.365	<5	<2	1.59	62	0.7	0.17	455	<5	<1
L398276	0.285	<5	<2	1.99	25	0.8	0.07	866	<5	<1
L398277	0.315	<5	<2	2.00	14	0.7	0.14	467	<5	<1
L398278	0.300	<5	<2	2.30	7	1.1	0.17	1000	<5	<1
L398279	0.360	<5	<2	1.18	9	<0.5	0.08	155	<5	<1
L398280	0.370	<5	<2	1.63	8	0.9	0.19	788	<5	<1
L398281	0.350	<5	<2	1.38	13	0.6	0.12	557	<5	<1
L398282	0.280	8	<2	1.55	9	0.8	0.15	680	<5	<1
L398283	0.325	9	<2	1.89	15	0.7	0.30	572	<5	<1
L398284	0.310	10	<2	1.95	12	0.7	0.23	633	<5	<1
L398285	0.315	<5	<2	1.31	6	<0.5	0.10	305	<5	<1
L398286	0.360	<5	<2	2.86	<3	0.8	0.46	1380	<5	<1
L398287	0.340	7	<2	1.86	5	0.6	0.08	247	<5	<1
L398288	0.290	<5	<2	1.93	10	0.5	0.21	650	<5	<1
L398289	0.295	<5	<2	1.57	7	0.6	0.51	539	<5	<1
L398290	0.310	11	<2	2.38	7	0.7	0.58	538	<5	<1
L398291	0.310	8	<2	1.61	13	0.6	0.42	460	<5	<1
L398292	0.305	9	<2	1.20	8	0.6	0.28	465	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121359 Order: PO#: SOLO-90403-05

Page 3 of 5

Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L398251	13	65	65.7	4.82	<1	0.37	18.9	15	1.01	486
L398252	7	45	61.8	3.57	2	0.32	15.8	11	0.62	397
L398253	4	24	33.1	2.16	<1	0.08	14.1	7	0.30	205
L398254	13	38	77.2	4.45	<1	0.07	21.4	7	0.30	518
L398255	12	43	60.2	4.30	1	0.11	18.3	24	0.73	390
L398256	12	35	55.4	3.20	<1	0.12	29.3	14	0.59	392
L398257	10	37	60.4	4.26	<1	0.35	28.3	18	0.77	310
L398258	11	37	77.7	3.41	<1	0.12	21.7	10	0.50	327
L398259	18	66	59.1	5.30	<1	1.04	34.4	28	1.49	471
L398260	6	32	75.5	3.00	<1	0.46	21.1	15	0.91	256
L398261	9	29	51.7	3.73	<1	0.25	23.9	18	0.81	506
L398262	8	34	32.7	3.15	<1	0.20	20.5	12	0.54	151
L398263	14	70	40.9	4.52	<1	0.33	23.5	18	0.84	288
L398264	14	44	62.3	4.46	<1	0.42	42.2	12	0.79	309
L398265	7	45	76.5	3.62	<1	0.29	25.5	8	0.41	244
L398266	10	33	79.0	4.42	<1	0.12	50.7	8	0.56	298
L398267	9	40	55.8	4.85	<1	0.10	25.7	6	0.23	341
L398268	9	30	23.6	3.20	<1	0.12	13.4	9	0.40	482
L398269	13	40	34.3	3.56	<1	0.12	17.6	13	0.60	497
L398270	6	46	71.8	3.88	2	0.28	23.6	7	0.58	141
L398271	9	36	34.9	3.14	<1	0.13	18.4	14	0.52	285
L398272	14	51	73.8	4.12	<1	0.07	11.4	14	0.58	310
L398273	23	37	42.4	3.32	1	0.25	25.8	14	0.43	416
L398274	11	66	55.0	3.20	<1	0.13	34.0	11	0.67	181
L398275	8	35	49.1	2.88	<1	0.04	18.9	8	0.41	196
L398276	8	54	78.9	3.26	<1	0.45	25.1	15	0.67	345
L398277	11	59	63.6	3.79	<1	0.21	17.2	16	0.81	345
L398278	10	67	80.7	4.05	2	0.48	36.0	12	1.06	334
L398279	6	30	36.9	2.89	<1	0.17	22.8	9	0.38	154
L398280	12	42	85.9	3.51	<1	0.28	25.9	10	0.82	526
L398281	8	35	92.2	2.89	<1	0.43	25.5	8	0.68	376
L398282	11	45	56.4	4.53	<1	0.50	17.7	12	0.91	528
L398283	12	50	51.9	3.69	1	0.09	17.6	17	0.72	407
L398284	12	50	63.2	3.63	<1	0.48	16.7	14	0.89	295
L398285	6	18	35.8	2.44	<1	0.23	10.1	11	0.42	659
L398286	11	131	67.1	4.81	<1	1.04	27.6	21	1.62	277
L398287	14	39	53.4	3.65	<1	0.92	43.6	13	0.99	503
L398288	16	33	42.4	3.05	<1	0.07	10.1	13	0.57	330
L398289	13	17	80.8	3.35	<1	0.06	12.5	12	0.45	223
L398290	18	40	55.1	4.58	<1	0.62	29.6	22	1.17	297
L398291	7	42	77.9	3.54	<1	0.21	24.1	11	0.79	399
L398292	12	67	48.4	3.67	1	0.25	22.8	10	0.60	315

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L398251	3	0.01	50	0.08	3	0.01	<5	8.0	<10	26.6
L398252	3	0.01	30	0.06	7	0.07	<5	5.9	<10	22.6
L398253	2	0.01	14	0.05	9	0.02	<5	3.0	<10	27.5
L398254	5	<0.01	51	0.04	10	<0.01	<5	6.4	<10	36.6
L398255	2	0.02	34	0.04	8	<0.01	<5	4.9	<10	29.1
L398256	1	0.01	35	0.02	6	<0.01	<5	6.6	<10	27.1
L398257	4	<0.01	32	0.11	11	0.05	<5	4.4	<10	30.2
L398258	3	<0.01	31	0.05	11	0.01	<5	4.8	<10	25.6
L398259	2	0.01	53	0.04	5	0.03	<5	6.6	<10	18.2
L398260	4	<0.01	23	0.05	9	0.03	<5	3.5	<10	15.7
L398261	3	0.01	21	0.14	16	0.04	<5	3.4	<10	22.8
L398262	<1	<0.01	26	0.03	9	0.07	<5	2.7	<10	10.4
L398263	<1	0.01	60	0.03	4	0.04	<5	4.3	<10	13.7
L398264	<1	0.01	54	0.05	9	0.08	<5	4.8	<10	12.0
L398265	3	<0.01	31	0.06	16	<0.01	<5	6.1	<10	26.1
L398266	2	<0.01	40	0.06	7	<0.01	<5	6.9	<10	19.5
L398267	2	<0.01	46	0.07	7	<0.01	<5	7.3	<10	34.0
L398268	2	0.01	25	0.05	8	<0.01	<5	3.2	<10	27.5
L398269	2	0.01	29	0.05	7	<0.01	<5	3.9	<10	23.9
L398270	3	<0.01	32	0.05	5	0.02	<5	4.3	<10	14.4
L398271	2	<0.01	28	0.06	4	0.02	<5	3.6	<10	17.9
L398272	1	0.01	45	0.04	6	<0.01	<5	4.7	<10	13.0
L398273	<1	<0.01	53	0.08	26	<0.01	<5	3.5	<10	34.2
L398274	<1	<0.01	39	0.04	10	<0.01	<5	5.6	<10	43.1
L398275	2	<0.01	26	0.03	9	<0.01	<5	5.7	<10	27.1
L398276	3	<0.01	41	0.06	9	<0.01	<5	6.8	<10	25.3
L398277	2	<0.01	54	0.04	6	<0.01	<5	6.1	<10	21.5
L398278	2	<0.01	53	0.07	8	<0.01	<5	6.5	<10	22.2
L398279	<1	<0.01	25	0.03	5	<0.01	<5	3.8	<10	19.0
L398280	2	<0.01	46	0.04	5	0.03	<5	10.6	<10	24.9
L398281	2	<0.01	27	0.05	5	0.03	<5	6.9	<10	25.6
L398282	2	<0.01	50	0.05	3	0.02	<5	5.9	<10	16.4
L398283	2	0.01	41	0.04	5	<0.01	<5	7.9	<10	25.6
L398284	2	0.01	40	0.05	3	0.03	<5	5.5	<10	24.3
L398285	2	<0.01	19	0.03	<2	<0.01	<5	3.5	<10	9.2
L398286	<1	0.01	57	0.13	<2	0.02	<5	9.6	<10	21.5
L398287	<1	<0.01	36	0.01	3	<0.01	<5	5.6	<10	8.4
L398288	1	0.01	24	0.03	4	<0.01	<5	3.2	<10	17.4
L398289	<1	0.02	17	0.14	<2	<0.01	<5	3.2	<10	35.5
L398290	<1	0.01	33	0.16	2	<0.01	<5	8.2	<10	35.0
L398291	2	0.01	32	0.09	<2	0.10	<5	6.8	<10	37.2
L398292	1	<0.01	79	0.08	5	<0.01	<5	5.6	<10	19.1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121359 Order: PO#: SOLO-90403-05

Page 5 of 5

Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L398251	0.13	108	<10	12.3	93	6.5
L398252	0.09	97	<10	11.0	153	2.4
L398253	0.07	62	<10	6.2	47	1.0
L398254	0.04	93	<10	10.3	133	2.6
L398255	0.12	92	<10	7.9	67	9.2
L398256	0.10	56	<10	17.0	62	7.4
L398257	0.10	72	<10	7.3	76	3.3
L398258	0.07	72	<10	7.7	75	5.6
L398259	0.22	73	<10	7.5	107	4.6
L398260	0.08	79	<10	5.2	65	2.6
L398261	0.09	92	<10	12.1	105	1.2
L398262	0.07	49	<10	5.4	116	5.5
L398263	0.11	78	<10	6.8	107	6.9
L398264	0.09	64	<10	11.2	127	5.0
L398265	0.04	52	<10	8.6	80	1.2
L398266	0.07	50	<10	14.1	84	6.0
L398267	0.03	94	<10	9.4	132	0.9
L398268	0.07	68	<10	4.0	83	0.9
L398269	0.10	74	<10	5.1	86	3.9
L398270	0.08	83	<10	6.2	98	3.3
L398271	0.08	79	<10	4.6	109	3.0
L398272	0.09	82	<10	4.6	65	16.9
L398273	0.05	71	<10	28.9	174	2.2
L398274	0.10	82	<10	19.8	116	7.5
L398275	0.07	68	<10	8.6	50	8.3
L398276	0.10	92	<10	12.0	141	3.3
L398277	0.10	90	<10	8.3	102	4.5
L398278	0.12	127	<10	16.9	188	3.6
L398279	0.06	52	<10	6.2	77	2.5
L398280	0.10	70	<10	19.3	118	5.8
L398281	0.09	69	<10	10.1	78	3.2
L398282	0.08	65	<10	6.0	113	3.8
L398283	0.12	78	<10	14.7	67	7.8
L398284	0.13	86	<10	7.2	73	5.8
L398285	0.06	30	<10	5.6	48	1.4
L398286	0.21	115	<10	18.9	106	2.1
L398287	0.12	30	<10	13.2	108	2.1
L398288	0.10	75	<10	2.7	43	5.1
L398289	0.10	60	<10	5.7	37	3.4
L398290	0.18	119	<10	13.2	79	7.0
L398291	0.09	81	<10	15.3	98	8.9
L398292	0.09	68	<10	14.1	96	4.5

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.