



Certificate of Analysis

Work Order: VC121414

To: **Kendra Johnston**
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA STREET
VACOUVER BC V6B 4N8

Date: Jul 31, 2012

P.O. No. : PO#: SOLO-90403-05/YK004-SOLO-Piano
Project No. : -
No. Of Samples : 71
Date Submitted : Jun 28, 2012
Report Comprises : Pages 1 to 9
(Inclusive of Cover Sheet)

Distribution of unused material:

Active files - upstairs:

Certified By :



Satpaul Gill
QAQC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method
M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion
Methods marked with an asterisk (e.g. *NAA08V) were subcontracted
Methods marked with the @ symbol (e.g. @AAS21E) denote accredited tests

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	WtKg WGH79 0.001 kg	Au FAA313 5 ppb	Ag ICP14B 2 ppm	Al ICP14B 0.01 %	As ICP14B 3 ppm	Be ICP14B 0.5 ppm	Ca ICP14B 0.01 %	Ba ICP14B 5 ppm	Bi ICP14B 5 ppm	Cd ICP14B 1 ppm
L398210	0.290	19	<2	2.62	8	0.8	0.55	662	<5	1
L398211	0.330	10	<2	2.06	10	0.6	0.55	380	<5	<1
L398212	0.410	6	<2	1.84	6	0.5	0.52	272	<5	<1
L398213	0.270	14	<2	1.95	4	0.6	0.47	277	<5	<1
L398214	0.445	<5	<2	1.98	15	0.7	0.35	339	<5	<1
L398215	0.380	<5	<2	2.28	41	0.8	0.31	395	<5	<1
L398216	0.400	<5	<2	2.01	22	1.0	0.43	460	<5	<1
L398217	0.280	11	<2	1.56	41	<0.5	0.18	304	<5	<1
L398218	0.325	5	<2	2.19	22	0.5	0.25	403	<5	<1
L398219	0.305	15	<2	1.16	26	<0.5	0.10	435	<5	<1
L398220	0.300	13	<2	1.82	12	0.7	0.11	816	<5	<1
L398221	0.225	9	<2	2.42	4	0.7	0.19	525	<5	<1
L398222	0.280	<5	<2	2.25	5	0.8	0.24	607	<5	<1
L398223	0.370	8	<2	2.62	4	0.9	0.29	2280	<5	2
L398224	0.345	<5	<2	2.75	5	0.7	0.23	376	<5	<1
L398225	0.380	<5	<2	2.48	16	0.7	0.24	399	<5	<1
L398226	0.405	10	<2	2.13	13	0.6	0.18	423	<5	<1
L398227	0.390	13	<2	2.48	3	0.7	0.37	470	<5	<1
L398228	0.330	16	<2	2.59	6	0.7	0.40	757	<5	1
L398229	0.285	<5	<2	2.05	12	0.6	0.22	468	<5	<1
L398230	0.420	7	<2	1.45	19	<0.5	0.09	390	<5	<1
L398231	0.475	<5	<2	1.70	16	0.7	0.12	311	<5	<1
L398232	0.395	6	<2	1.56	17	<0.5	0.21	321	<5	<1
L398233	0.375	<5	<2	1.99	21	0.8	0.28	343	<5	<1
L398234	0.560	<5	<2	1.53	23	0.5	0.18	308	<5	<1
L398235	0.405	<5	<2	1.75	14	<0.5	0.29	242	<5	<1
L398236	0.400	8	<2	1.68	5	<0.5	0.52	230	<5	<1
L398237	0.460	<5	<2	1.85	4	0.7	0.50	380	<5	<1
L398238	0.280	<5	<2	1.72	6	0.5	0.57	333	<5	<1
L398239	0.465	<5	<2	1.85	11	0.6	0.27	265	<5	<1
L398240	0.490	<5	<2	1.73	19	0.6	0.31	297	<5	<1
L398241	0.605	6	<2	1.77	10	0.5	0.37	272	<5	<1
L398242	0.395	5	<2	2.37	15	0.7	0.40	505	<5	<1
L398243	0.375	11	<2	1.89	35	0.7	0.25	564	<5	<1
L398244	0.505	<5	<2	1.38	34	0.7	0.12	462	<5	<1
L398245	0.605	<5	<2	1.80	48	<0.5	0.17	359	<5	<1
L398246	0.335	7	<2	1.76	34	0.7	0.20	523	<5	<1
L398247	0.360	<5	<2	2.45	8	0.9	0.32	743	<5	1
L398248	0.450	5	<2	2.10	14	0.7	0.26	1020	<5	<1
L398249	0.320	9	<2	2.87	18	0.8	0.22	373	<5	<1
L398250	0.275	9	<2	2.69	20	0.7	0.20	350	<5	<1
L398110	0.310	<5	<2	2.38	<3	1.3	0.23	150	<5	<1
L398111	0.315	<5	<2	2.24	<3	2.7	0.51	258	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	WtKg WGH79 0.001 kg	Au FAA313 5 ppb	Ag ICP14B 2 ppm	Al ICP14B 0.01 %	As ICP14B 3 ppm	Be ICP14B 0.5 ppm	Ca ICP14B 0.01 %	Ba ICP14B 5 ppm	Bi ICP14B 5 ppm	Cd ICP14B 1 ppm
L398112	0.350	<5	<2	2.45	<3	1.7	0.31	196	<5	<1
L398113	0.330	6	<2	2.01	9	0.9	0.38	311	<5	1
L398114	0.350	<5	<2	1.93	4	1.3	0.27	262	<5	<1
L398115	0.260	<5	<2	1.55	<3	1.1	0.22	115	<5	<1
L398116	0.315	<5	<2	2.18	4	1.0	0.17	186	<5	<1
L398117	0.285	<5	<2	2.09	6	0.8	0.22	204	<5	<1
L398118	0.345	<5	<2	2.07	6	0.9	0.26	538	<5	<1
L398119	0.270	<5	<2	1.62	4	0.7	0.22	300	<5	<1
L398120	0.330	<5	<2	1.66	14	0.6	0.26	181	<5	<1
L398121	0.285	5	<2	2.12	23	0.7	0.24	208	<5	<1
L398122	0.350	<5	<2	2.18	7	1.0	0.40	272	<5	<1
L398123	0.390	<5	<2	1.81	14	0.6	0.30	256	<5	<1
L398124	0.355	<5	<2	2.77	14	0.7	0.14	572	<5	<1
L398125	0.295	<5	<2	2.12	15	1.1	0.10	335	<5	2
L398126	0.305	5	<2	2.14	14	0.8	0.14	220	<5	1
L398127	0.315	5	<2	1.91	9	0.8	0.23	459	<5	<1
L398128	0.275	<5	<2	3.42	8	0.8	0.22	927	<5	<1
L398129	0.245	<5	<2	2.19	8	0.6	0.19	873	<5	1
L398130	0.305	<5	<2	1.46	37	1.2	0.43	1260	<5	2
L398131	0.365	<5	<2	2.59	28	1.0	0.18	270	<5	<1
L398132	0.320	<5	<2	1.96	10	0.6	0.20	424	<5	<1
L398133	0.355	<5	<2	2.17	13	0.7	0.36	473	<5	<1
L398134	0.315	<5	<2	2.45	10	0.8	0.47	459	<5	1
L398135	0.265	<5	<2	2.33	3	0.7	0.64	323	<5	<1
L398136	0.405	<5	<2	2.95	7	0.9	0.23	410	<5	<1
L398137	0.360	<5	<2	2.99	30	0.7	0.23	571	<5	<1
L398138	0.355	6	<2	2.25	6	0.8	0.13	722	<5	1
L398139	0.305	8	<2	2.12	10	0.6	0.20	343	<5	<1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L398210	14	47	69.7	4.48	<1	0.47	10.1	17	1.40	554
L398211	12	39	89.2	3.66	1	0.29	13.4	14	0.85	358
L398212	9	32	30.1	3.02	2	0.08	11.9	12	0.60	294
L398213	9	29	32.0	2.78	<1	0.11	12.1	9	0.52	223
L398214	8	41	38.5	2.81	<1	0.16	16.2	9	0.48	185
L398215	14	60	53.3	3.49	<1	0.35	24.2	10	0.74	356
L398216	12	55	48.9	3.71	1	0.50	33.3	10	0.84	413
L398217	8	32	26.4	3.01	<1	0.14	13.5	12	0.49	263
L398218	8	44	34.9	3.45	3	0.06	11.5	14	0.61	197
L398219	6	30	49.0	2.52	1	0.25	17.7	9	0.46	157
L398220	7	62	66.5	3.79	<1	0.34	18.3	14	0.87	286
L398221	16	38	59.0	4.02	1	0.57	29.1	24	1.05	478
L398222	11	76	78.0	4.02	<1	0.58	23.7	20	1.19	414
L398223	14	56	97.7	5.35	1	0.47	29.6	14	0.98	531
L398224	12	43	78.0	4.66	<1	1.07	19.4	26	1.52	507
L398225	15	60	65.6	4.30	<1	0.15	17.7	23	0.96	533
L398226	10	47	41.8	3.63	<1	0.11	12.4	15	0.67	279
L398227	15	55	89.3	4.72	<1	0.57	19.6	18	1.30	430
L398228	15	42	80.9	4.55	1	0.94	33.5	26	1.28	385
L398229	10	41	33.8	3.43	1	0.12	7.9	15	0.65	512
L398230	5	31	45.7	2.86	<1	0.21	14.6	13	0.47	124
L398231	13	38	40.3	2.94	1	0.43	27.1	8	0.73	397
L398232	9	29	24.7	2.70	<1	0.08	12.5	10	0.43	326
L398233	10	48	37.7	3.20	<1	0.39	24.5	9	0.72	339
L398234	6	34	33.1	2.60	<1	0.27	17.6	7	0.41	170
L398235	6	30	26.3	2.27	<1	0.13	12.8	7	0.39	116
L398236	9	30	21.5	2.76	<1	0.04	11.0	11	0.54	291
L398237	13	34	42.6	3.30	<1	0.38	10.7	12	0.76	324
L398238	7	27	30.6	2.75	<1	0.05	11.3	10	0.50	196
L398239	6	35	34.8	2.22	<1	0.23	15.0	6	0.40	108
L398240	8	45	36.2	2.75	<1	0.20	15.6	8	0.57	203
L398241	10	61	44.2	2.89	2	0.21	17.5	12	0.83	227
L398242	14	77	55.1	4.04	<1	0.53	28.0	12	1.08	394
L398243	10	63	57.8	3.41	1	0.27	25.7	10	0.68	303
L398244	5	36	60.5	3.25	2	0.40	26.7	7	0.57	162
L398245	10	42	50.1	3.27	<1	0.17	13.4	15	0.56	313
L398246	8	48	61.9	3.42	<1	0.29	16.7	13	0.66	232
L398247	18	47	96.0	5.25	<1	0.82	26.2	15	1.19	768
L398248	10	47	69.6	3.77	2	0.08	17.9	12	0.66	406
L398249	14	51	75.9	4.00	1	0.06	14.9	15	0.56	460
L398250	14	50	74.5	3.82	1	0.06	12.2	14	0.53	480
L398110	11	28	12.2	3.76	<1	0.84	4.1	34	1.09	842
L398111	8	30	19.0	3.95	<1	0.81	13.8	27	1.27	794

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121414 Order: PO#: SOLO-90403-05/YK004-SOLO-Piano

Page 5 of 9

Element Method Det.Lim. Units	Co ICP14B 1 ppm	Cr ICP14B 1 ppm	Cu ICP14B 0.5 ppm	Fe ICP14B 0.01 %	Hg ICP14B 1 ppm	K ICP14B 0.01 %	La ICP14B 0.5 ppm	Li ICP14B 1 ppm	Mg ICP14B 0.01 %	Mn ICP14B 2 ppm
L398112	11	32	10.3	3.86	2	0.95	6.8	32	1.38	682
L398113	12	41	31.9	3.45	2	0.05	17.6	17	0.69	464
L398114	10	37	25.2	3.18	<1	0.08	21.9	14	0.56	375
L398115	8	25	15.0	2.58	<1	0.21	24.8	12	0.47	291
L398116	9	35	16.7	3.08	<1	0.15	8.9	16	0.65	265
L398117	8	32	17.7	2.98	<1	0.05	11.8	16	0.57	217
L398118	12	49	63.8	3.59	<1	0.09	31.4	15	0.66	322
L398119	10	39	30.1	2.59	2	0.19	17.3	11	0.59	232
L398120	13	37	42.3	3.16	<1	0.05	14.6	11	0.47	469
L398121	14	42	41.7	3.36	1	0.06	12.3	13	0.54	533
L398122	21	42	84.9	4.16	<1	0.52	41.6	12	0.99	523
L398123	10	44	37.6	3.15	1	0.16	18.7	12	0.64	262
L398124	8	71	86.9	4.88	<1	1.02	28.4	28	1.31	218
L398125	4	49	94.0	5.11	1	0.37	29.1	16	0.76	152
L398126	9	60	88.8	4.71	1	0.23	28.5	19	0.85	357
L398127	11	58	67.3	4.27	<1	0.53	28.8	18	0.90	282
L398128	20	112	82.6	5.34	<1	1.19	22.4	37	2.13	373
L398129	12	49	59.2	3.82	<1	0.36	21.0	19	0.82	275
L398130	10	37	57.1	3.71	<1	0.13	26.2	15	0.52	265
L398131	18	189	51.8	4.09	1	0.47	26.7	31	1.65	243
L398132	10	56	36.7	3.58	<1	0.29	20.9	23	0.74	246
L398133	13	70	58.4	4.18	<1	0.85	37.4	27	1.01	368
L398134	14	78	56.8	4.65	<1	1.10	43.1	31	1.24	358
L398135	21	58	25.8	4.49	2	0.48	17.2	34	1.26	494
L398136	16	130	41.3	4.59	2	1.09	13.4	33	1.70	496
L398137	17	120	58.9	4.13	<1	1.05	9.6	39	1.97	473
L398138	9	64	95.0	4.38	<1	0.77	38.8	17	1.11	337
L398139	19	40	19.6	3.85	1	0.13	15.3	17	0.73	416

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L398210	<1	0.03	23	0.08	2	<0.01	<5	11.6	<10	39.8
L398211	<1	0.03	21	0.07	4	<0.01	<5	8.9	<10	37.9
L398212	<1	0.03	17	0.06	4	<0.01	<5	6.0	<10	38.2
L398213	<1	0.03	16	0.04	7	<0.01	<5	5.6	<10	37.0
L398214	<1	0.03	28	0.02	5	<0.01	<5	5.7	<10	30.4
L398215	1	0.02	44	0.05	9	<0.01	<5	6.3	<10	26.7
L398216	<1	0.02	46	0.10	7	<0.01	<5	6.6	<10	25.4
L398217	1	0.02	20	0.04	6	<0.01	<5	3.2	<10	18.9
L398218	1	0.02	22	0.02	9	<0.01	<5	5.4	<10	26.8
L398219	2	0.02	18	0.03	6	0.05	<5	3.1	<10	15.5
L398220	3	0.02	32	0.06	10	0.16	<5	6.3	<10	21.6
L398221	<1	0.02	32	0.05	2	<0.01	<5	7.8	<10	19.5
L398222	2	0.02	40	0.11	8	0.05	<5	5.8	<10	25.4
L398223	2	0.01	257	0.07	5	<0.01	<5	13.2	<10	34.5
L398224	2	0.02	25	0.08	5	0.15	<5	5.5	<10	21.7
L398225	2	0.02	51	0.04	5	0.01	<5	7.6	<10	22.9
L398226	2	0.02	33	0.03	5	0.02	<5	5.2	<10	20.8
L398227	<1	0.02	34	0.13	3	0.05	<5	6.6	<10	38.5
L398228	2	0.02	35	0.18	3	0.03	<5	6.8	<10	28.0
L398229	1	0.02	34	0.04	7	0.01	<5	3.9	<10	19.6
L398230	2	0.02	22	0.03	4	0.08	<5	2.6	<10	14.5
L398231	2	0.02	22	0.04	9	0.03	<5	4.2	<10	18.0
L398232	2	0.02	17	0.04	7	<0.01	<5	3.4	<10	20.5
L398233	<1	0.02	28	0.04	5	<0.01	<5	5.4	<10	22.1
L398234	<1	0.02	20	0.03	6	<0.01	<5	3.9	<10	24.5
L398235	<1	0.02	16	0.02	5	<0.01	<5	3.6	<10	27.1
L398236	<1	0.03	16	0.06	4	<0.01	<5	5.0	<10	35.6
L398237	<1	0.03	18	0.07	6	<0.01	<5	7.2	<10	40.1
L398238	<1	0.03	17	0.05	6	<0.01	<5	5.0	<10	42.4
L398239	<1	0.02	21	0.01	6	<0.01	<5	4.5	<10	25.4
L398240	<1	0.02	27	0.02	7	<0.01	<5	4.9	<10	26.9
L398241	<1	0.02	34	0.03	4	<0.01	<5	5.4	<10	24.0
L398242	<1	0.02	47	0.08	3	<0.01	<5	6.1	<10	25.2
L398243	1	0.02	36	0.06	6	0.03	<5	7.4	<10	26.5
L398244	2	0.02	27	0.04	9	0.02	<5	5.3	<10	22.6
L398245	3	0.02	33	0.04	4	0.02	<5	4.0	<10	22.7
L398246	1	0.02	30	0.05	3	0.03	<5	6.6	<10	24.1
L398247	2	0.02	52	0.12	7	0.06	<5	9.3	<10	35.2
L398248	2	0.02	29	0.03	6	<0.01	<5	9.2	<10	30.1
L398249	2	0.02	50	0.06	10	0.01	<5	7.2	<10	21.9
L398250	2	0.02	50	0.06	5	0.01	<5	5.2	<10	20.9
L398110	<1	0.02	11	0.08	8	<0.01	<5	1.8	<10	22.1
L398111	<1	0.02	13	0.15	6	<0.01	<5	4.1	<10	51.4

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121414 Order: PO#: SOLO-90403-05/YK004-SOLO-Piano

Page 7 of 9

Element Method Det.Lim. Units	Mo ICP14B 1 ppm	Na ICP14B 0.01 %	Ni ICP14B 1 ppm	P ICP14B 0.01 %	Pb ICP14B 2 ppm	S ICP14B 0.01 %	Sb ICP14B 5 ppm	Sc ICP14B 0.5 ppm	Sn ICP14B 10 ppm	Sr ICP14B 0.5 ppm
L398112	<1	0.02	14	0.08	2	<0.01	<5	2.5	<10	38.0
L398113	<1	0.02	25	0.05	9	<0.01	<5	8.1	<10	36.9
L398114	<1	0.02	20	0.03	12	<0.01	<5	6.5	<10	25.4
L398115	<1	0.02	15	0.05	16	<0.01	<5	3.5	<10	16.3
L398116	<1	0.02	18	0.02	5	<0.01	<5	3.4	<10	17.4
L398117	<1	0.02	19	0.03	8	<0.01	<5	4.5	<10	19.5
L398118	<1	0.02	36	0.04	10	<0.01	<5	9.9	<10	25.5
L398119	<1	0.02	23	0.05	6	<0.01	<5	4.3	<10	19.8
L398120	<1	0.02	31	0.05	6	<0.01	<5	6.2	<10	25.8
L398121	<1	0.02	46	0.04	5	<0.01	<5	4.6	<10	24.7
L398122	3	0.02	60	0.12	7	<0.01	<5	6.4	<10	24.9
L398123	1	0.02	32	0.07	7	<0.01	<5	4.5	<10	24.4
L398124	2	0.04	25	0.07	3	0.25	<5	6.3	<10	20.9
L398125	18	0.03	24	0.10	5	0.37	<5	3.4	<10	36.0
L398126	3	0.02	53	0.09	8	0.06	<5	3.7	<10	18.2
L398127	3	0.02	47	0.10	6	0.05	<5	4.6	<10	24.5
L398128	<1	0.02	65	0.04	<2	<0.01	<5	13.0	<10	15.0
L398129	2	0.02	43	0.09	6	0.03	<5	4.3	<10	22.5
L398130	1	0.01	66	0.13	10	<0.01	6	4.7	<10	29.4
L398131	<1	0.02	157	0.05	6	0.02	<5	6.3	<10	16.8
L398132	1	0.02	39	0.03	6	<0.01	<5	4.0	<10	16.7
L398133	1	0.02	47	0.11	5	0.07	<5	4.5	<10	23.4
L398134	<1	0.02	64	0.13	8	<0.01	<5	4.6	<10	22.4
L398135	<1	0.02	45	0.07	5	<0.01	<5	3.6	<10	26.0
L398136	<1	0.01	90	0.09	4	<0.01	<5	4.2	<10	12.7
L398137	<1	0.01	46	0.04	<2	<0.01	<5	5.0	<10	14.7
L398138	3	0.02	35	0.09	5	0.22	<5	5.1	<10	21.5
L398139	<1	0.02	31	0.04	7	<0.01	<5	3.1	<10	19.2

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121414 Order: PO#: SOLO-90403-05/YK004-SOLO-Piano

Page 8 of 9

Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L398210	0.17	118	<10	10.8	307	12.6
L398211	0.15	92	<10	10.0	78	13.0
L398212	0.12	74	<10	7.7	57	6.3
L398213	0.10	64	<10	7.3	59	6.4
L398214	0.10	56	<10	9.5	55	16.7
L398215	0.14	72	<10	11.9	74	21.4
L398216	0.11	74	<10	16.2	98	13.6
L398217	0.09	67	<10	4.7	62	7.7
L398218	0.12	81	<10	5.6	60	16.7
L398219	0.08	52	<10	4.0	61	7.0
L398220	0.09	86	<10	7.1	111	7.3
L398221	0.15	64	<10	13.2	100	8.4
L398222	0.18	115	<10	7.6	77	4.4
L398223	0.11	140	<10	35.7	463	4.1
L398224	0.20	143	<10	5.5	84	3.2
L398225	0.13	99	<10	13.4	81	8.3
L398226	0.11	100	<10	5.3	85	7.1
L398227	0.16	170	<10	8.6	102	3.4
L398228	0.19	123	<10	15.2	115	4.7
L398229	0.10	77	<10	3.0	60	8.8
L398230	0.08	56	<10	3.1	60	5.7
L398231	0.10	60	<10	8.3	95	8.3
L398232	0.09	56	<10	5.6	51	5.0
L398233	0.13	70	<10	11.9	76	12.3
L398234	0.10	55	<10	8.4	55	13.8
L398235	0.08	46	<10	6.4	47	2.4
L398236	0.12	68	<10	6.6	53	4.2
L398237	0.12	84	<10	8.1	86	16.3
L398238	0.10	61	<10	7.2	48	2.6
L398239	0.05	45	<10	8.2	48	14.6
L398240	0.11	60	<10	8.0	54	13.5
L398241	0.13	68	<10	12.1	49	9.6
L398242	0.16	75	<10	11.6	77	8.9
L398243	0.11	94	<10	16.3	102	14.0
L398244	0.09	59	<10	13.2	109	9.7
L398245	0.11	79	<10	5.3	103	9.8
L398246	0.14	88	<10	10.2	95	11.0
L398247	0.16	113	<10	21.4	160	6.9
L398248	0.12	87	<10	19.4	59	10.6
L398249	0.09	91	<10	12.0	56	9.0
L398250	0.08	85	<10	8.5	58	9.2
L398110	0.17	62	<10	1.8	108	3.2
L398111	0.12	63	<10	7.7	142	5.0

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Final : VC121414 Order: PO#: SOLO-90403-05/YK004-SOLO-Piano

Page 9 of 9

Element Method Det.Lim. Units	Ti ICP14B 0.01 %	V ICP14B 1 ppm	W ICP14B 10 ppm	Y ICP14B 0.5 ppm	Zn ICP14B 1 ppm	Zr ICP14B 0.5 ppm
L398112	0.15	58	<10	3.0	129	3.8
L398113	0.10	72	<10	11.9	53	10.5
L398114	0.09	66	<10	12.0	52	7.8
L398115	0.08	42	<10	8.0	61	4.8
L398116	0.10	60	<10	3.0	64	8.0
L398117	0.09	61	<10	5.8	46	4.3
L398118	0.10	77	<10	29.9	78	9.7
L398119	0.10	62	<10	9.1	81	1.3
L398120	0.07	59	<10	7.9	70	1.9
L398121	0.09	68	<10	4.3	65	4.0
L398122	0.10	73	<10	20.8	89	6.3
L398123	0.09	65	<10	8.5	86	2.6
L398124	0.19	112	<10	8.1	106	4.4
L398125	0.06	153	<10	14.2	175	2.6
L398126	0.05	104	<10	10.1	116	2.4
L398127	0.11	110	<10	14.0	119	1.9
L398128	0.28	118	10	9.7	74	4.1
L398129	0.12	91	<10	7.4	118	6.0
L398130	0.01	92	<10	9.4	192	2.5
L398131	0.15	98	<10	5.7	86	4.8
L398132	0.12	83	<10	8.4	70	1.6
L398133	0.18	93	<10	11.2	117	3.8
L398134	0.19	89	<10	14.9	129	3.7
L398135	0.16	66	<10	5.3	82	3.6
L398136	0.19	100	<10	6.0	116	3.9
L398137	0.19	105	<10	3.0	96	3.7
L398138	0.13	126	<10	17.3	131	3.8
L398139	0.09	69	<10	4.0	71	2.1

This document is issued by the Company under its General Conditions of Service accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.