

Acme Analytical Laboratories (Vancouver) Ltd.  
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA  
PHONE (604) 253-3158

**Client:** **Goldstrike Resources Ltd.**  
1300 - 1111 West Georgia Street  
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List  
Receiving Lab: Canada-Whitehorse  
Received: July 03, 2013  
Report Date: August 23, 2013  
Page: 1 of 2

## CERTIFICATE OF ANALYSIS

WHI13000088.1

### CLIENT JOB INFORMATION

Project: Plateau South  
Shipment ID: PLAS\_CHANNEL\_2013\_1  
P.O. Number  
Number of Samples: 29

### SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days  
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.  
1300 - 1111 West Georgia Street  
Vancouver BC V6E 4M3  
CANADA

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	29	Crush, split and pulverize 250 g rock to 200 mesh			WHI
3B	29	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1DX	29	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.  
\*\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

# CERTIFICATE OF ANALYSIS

WHI13000088.1

	Method Analyte Unit MDL	WGHT Wgt kg 0.01	3B Au ppb 2	1DX Mo ppm 0.1	1DX Cu ppm 0.1	1DX Pb ppm 0.1	1DX Zn ppm 1	1DX Ag ppm 0.1	1DX Ni ppm 0.1	1DX Co ppm 0.1	1DX Mn ppm 1	1DX Fe % 0.01	1DX As ppm 0.5	1DX Au ppb 0.5	1DX Th ppm 0.1	1DX Sr ppm 1	1DX Cd ppm 0.1	1DX Sb ppm 0.1	1DX Bi ppm 0.1	1DX V ppm 2	1DX Ca % 0.01
1243701	Rock	1.07	<2	0.1	1.0	19.8	24	<0.1	3.2	1.3	334	0.80	4.9	<0.5	5.3	12	<0.1	<0.1	0.2	5	0.33
1243702	Rock	0.84	6	0.1	2.6	52.9	12	0.2	2.9	1.6	152	0.52	137.3	14.1	4.5	10	<0.1	<0.1	0.6	<2	0.13
1243703	Rock	0.73	4	0.2	5.0	20.8	8	<0.1	2.3	1.1	145	0.70	34.5	1.8	2.8	7	<0.1	<0.1	0.2	<2	0.11
1243704	Rock	1.15	386	0.2	3.1	17.6	14	<0.1	3.6	1.4	162	0.85	227.6	243.9	3.5	7	0.2	0.1	0.2	<2	0.06
1243705	Rock	1.38	5	0.4	24.7	8.9	75	<0.1	13.8	6.8	166	3.71	31.8	16.3	12.6	7	<0.1	0.2	0.2	14	0.02
1243706	Rock	1.56	<2	0.4	22.6	11.9	92	<0.1	11.4	5.6	205	4.83	13.7	3.5	11.0	7	<0.1	0.1	0.3	17	0.02
1243707	Rock	1.23	<2	0.1	8.0	4.0	6	<0.1	2.7	2.5	167	0.64	77.7	5.3	2.9	18	<0.1	<0.1	<0.1	<2	0.23
1243708	Rock	1.78	13	0.2	21.8	54.1	17	0.2	5.5	3.5	186	1.32	88.5	28.3	2.6	8	<0.1	<0.1	0.7	<2	0.08
1243709	Rock	0.99	7	0.1	2.7	4.2	6	<0.1	3.4	2.0	144	0.56	251.4	3.5	3.5	13	<0.1	0.2	<0.1	<2	0.13
1243710	Rock	1.50	<2	<0.1	15.0	11.9	62	<0.1	12.8	5.2	274	2.73	95.7	1.9	4.6	3	<0.1	0.1	0.1	12	0.02
1243711	Rock	1.85	14	<0.1	15.9	10.6	44	<0.1	11.3	5.0	231	2.29	431.7	5.6	5.0	3	<0.1	0.2	0.1	8	0.02
1243712	Rock	0.76	12	0.3	4.9	4.3	6	<0.1	4.6	2.4	47	0.51	314.9	9.2	6.1	3	<0.1	0.3	<0.1	<2	0.01
1243713	Rock	1.35	11	<0.1	6.4	2.4	5	<0.1	3.6	2.2	127	0.58	284.3	2.7	5.5	7	<0.1	0.2	<0.1	<2	0.10
1243714	Rock	1.28	12	0.1	2.5	1.5	3	<0.1	0.9	1.9	90	0.37	628.3	7.0	0.9	2	<0.1	0.2	<0.1	<2	0.07
1243715	Rock	2.35	73	0.1	12.2	5.7	18	<0.1	7.0	3.6	221	1.37	1516	125.4	4.6	5	<0.1	0.4	<0.1	3	0.08
1243716	Rock	2.12	9	0.1	10.5	6.5	29	<0.1	6.4	3.7	365	1.58	176.3	10.1	4.7	5	<0.1	0.1	<0.1	7	0.07
1243717	Rock	1.84	21	0.1	5.3	32.1	9	<0.1	5.2	2.2	95	0.61	117.3	10.5	3.3	2	<0.1	<0.1	0.2	<2	0.02
1243718	Rock	0.79	<2	<0.1	1.4	1.1	3	<0.1	3.1	0.3	35	0.23	15.2	1.1	0.2	<1	<0.1	<0.1	<0.1	<2	<0.01
1243719	Rock	1.18	2	<0.1	4.2	29.8	10	<0.1	7.9	1.1	67	0.71	117.3	3.0	2.2	2	<0.1	<0.1	0.3	2	0.03
1243720	Rock	1.29	9	<0.1	3.7	3.9	18	<0.1	10.0	3.6	120	1.00	534.0	8.1	3.9	3	<0.1	0.1	<0.1	3	0.03
1243721	Rock	1.72	<2	<0.1	1.5	4.8	7	<0.1	1.9	0.9	92	0.45	33.6	2.0	1.8	<1	<0.1	<0.1	<0.1	<2	0.01
1243722	Rock	0.94	<2	0.2	10.0	2.8	53	<0.1	7.4	3.1	141	2.68	32.5	<0.5	6.6	7	<0.1	<0.1	<0.1	9	0.04
1243723	Rock	1.99	4	0.1	5.9	2.4	8	<0.1	4.6	2.0	138	0.83	36.3	1.4	1.4	6	<0.1	<0.1	<0.1	<2	0.09
1243724	Rock	2.69	3	0.1	6.4	7.9	14	<0.1	6.5	3.3	264	0.86	15.0	10.7	5.6	4	<0.1	<0.1	<0.1	4	0.05
1243725	Rock	1.06	18	0.2	4.2	19.0	10	<0.1	5.8	2.3	276	0.92	1298	15.9	4.6	13	<0.1	0.3	0.2	2	0.22
1243726	Rock	1.77	69	0.3	28.7	3.7	71	<0.1	15.7	6.2	253	4.58	143.0	11.1	18.9	9	<0.1	<0.1	0.1	16	0.04
1243727	Rock	1.97	11	0.1	23.7	6.0	88	<0.1	16.6	5.8	391	4.81	593.5	5.6	11.1	6	<0.1	0.2	<0.1	18	0.05
1243728	Rock	1.38	99	0.2	17.0	10.5	49	<0.1	10.5	4.7	265	3.28	3644	103.8	7.1	6	<0.1	0.9	<0.1	12	0.03
1243729	Rock	3.05	43	0.1	2.3	4.8	20	<0.1	5.2	3.6	286	1.38	1793	25.4	4.5	6	<0.1	0.6	<0.1	3	0.16

# CERTIFICATE OF ANALYSIS

WHI13000088.1

	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga
	Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm
	MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1
1243701	Rock	0.013	9	9	0.16	8	<0.001	<20	0.25	0.028	<0.01	<0.1	<0.01	<0.1	<0.05	1.1	<0.5	<1
1243702	Rock	0.014	6	5	0.08	16	<0.001	<20	0.13	0.033	<0.01	<0.1	<0.01	<0.1	<0.05	0.6	<0.5	<1
1243703	Rock	0.006	4	4	0.08	48	<0.001	<20	0.15	0.034	<0.01	<0.1	<0.01	<0.1	<0.05	0.7	<0.5	<1
1243704	Rock	0.011	4	3	0.05	54	<0.001	<20	0.13	0.032	<0.01	<0.1	<0.01	<0.1	0.31	0.6	<0.5	<1
1243705	Rock	0.020	31	24	0.89	135	0.002	<20	1.77	0.008	0.13	<0.1	<0.01	<0.1	<0.05	1.6	<0.5	4
1243706	Rock	0.024	27	28	1.14	71	0.002	<20	2.09	0.006	0.13	<0.1	<0.01	<0.1	<0.05	1.8	<0.5	6
1243707	Rock	0.006	5	3	0.09	42	<0.001	<20	0.12	0.033	<0.01	<0.1	<0.01	<0.1	<0.05	0.5	<0.5	<1
1243708	Rock	0.007	3	4	0.21	110	<0.001	<20	0.38	0.017	<0.01	<0.1	<0.01	<0.1	0.12	1.2	<0.5	<1
1243709	Rock	0.007	5	4	0.09	46	<0.001	<20	0.14	0.029	<0.01	<0.1	<0.01	<0.1	<0.05	0.5	<0.5	<1
1243710	Rock	0.009	6	11	0.62	24	0.003	<20	1.16	0.022	0.01	<0.1	<0.01	<0.1	0.06	2.0	<0.5	4
1243711	Rock	0.010	5	9	0.44	38	0.001	<20	0.82	0.020	0.02	<0.1	<0.01	<0.1	0.13	1.8	<0.5	2
1243712	Rock	0.007	7	4	0.03	39	<0.001	<20	0.16	0.040	<0.01	<0.1	<0.01	<0.1	<0.05	0.8	<0.5	<1
1243713	Rock	0.012	7	4	0.06	82	<0.001	<20	0.15	0.041	<0.01	<0.1	<0.01	<0.1	<0.05	0.8	<0.5	<1
1243714	Rock	<0.001	2	2	0.02	11	<0.001	<20	0.06	0.014	<0.01	<0.1	<0.01	<0.1	<0.05	0.5	<0.5	<1
1243715	Rock	0.006	5	8	0.22	50	<0.001	<20	0.40	0.034	<0.01	<0.1	<0.01	<0.1	0.12	1.4	<0.5	1
1243716	Rock	0.009	6	10	0.29	41	0.001	<20	0.53	0.027	<0.01	<0.1	<0.01	<0.1	0.08	2.0	<0.5	2
1243717	Rock	0.004	3	4	0.04	28	<0.001	<20	0.10	0.022	<0.01	<0.1	<0.01	<0.1	<0.05	0.4	<0.5	<1
1243718	Rock	<0.001	<1	1	<0.01	3	<0.001	<20	0.01	0.001	<0.01	<0.1	<0.01	<0.1	<0.05	0.1	<0.5	<1
1243719	Rock	0.006	4	5	0.10	6	<0.001	<20	0.20	0.010	<0.01	<0.1	<0.01	<0.1	<0.05	0.5	<0.5	<1
1243720	Rock	0.013	6	6	0.16	8	<0.001	<20	0.33	0.021	0.01	<0.1	<0.01	<0.1	<0.05	0.8	<0.5	<1
1243721	Rock	0.004	1	3	0.03	3	<0.001	<20	0.08	0.010	<0.01	<0.1	<0.01	<0.1	<0.05	0.3	<0.5	<1
1243722	Rock	0.020	13	11	0.64	260	0.003	<20	1.27	0.005	0.11	<0.1	<0.01	<0.1	<0.05	1.4	<0.5	4
1243723	Rock	0.006	7	2	0.07	29	<0.001	<20	0.15	0.002	0.04	<0.1	0.01	<0.1	<0.05	0.8	<0.5	<1
1243724	Rock	0.010	8	7	0.12	46	<0.001	<20	0.28	0.021	0.03	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1
1243725	Rock	0.024	6	7	0.10	46	<0.001	<20	0.19	0.029	<0.01	<0.1	<0.01	<0.1	0.09	1.3	<0.5	<1
1243726	Rock	0.035	31	22	0.98	229	0.002	<20	1.92	0.006	0.16	0.6	<0.01	<0.1	0.05	2.3	<0.5	5
1243727	Rock	0.020	15	23	1.28	136	0.004	<20	2.29	0.009	0.07	<0.1	<0.01	<0.1	0.07	2.6	<0.5	8
1243728	Rock	0.013	7	14	0.58	109	0.001	<20	1.16	0.025	0.04	<0.1	<0.01	<0.1	0.18	2.4	0.9	4
1243729	Rock	0.009	6	4	0.12	58	<0.001	<20	0.32	0.034	0.02	<0.1	<0.01	<0.1	0.08	1.5	<0.5	<1

## QUALITY CONTROL REPORT

WHI13000088.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
Pulp Duplicates																					
REP G1-WHI	QC			<0.1	2.7	3.4	43	<0.1	2.7	4.0	551	1.88	<0.5	<0.5	4.7	49	<0.1	<0.1	<0.1	35	0.42
1243726	Rock	1.77	69	0.3	28.7	3.7	71	<0.1	15.7	6.2	253	4.58	143.0	11.1	18.9	9	<0.1	<0.1	0.1	16	0.04
REP 1243726	QC		62																		
Core Reject Duplicates																					
1243701	Rock	1.07	<2	0.1	1.0	19.8	24	<0.1	3.2	1.3	334	0.80	4.9	<0.5	5.3	12	<0.1	<0.1	0.2	5	0.33
DUP 1243701	QC		2	<0.1	0.9	17.8	24	0.1	3.5	1.3	341	0.87	5.2	213.0	5.4	12	<0.1	<0.1	0.3	5	0.31
Reference Materials																					
STD DS9	Standard			10.5	105.8	126.0	290	1.1	37.0	7.1	573	2.30	24.1	93.5	5.8	66	2.2	4.7	6.3	38	0.69
STD OREAS45EA	Standard			1.3	637.5	14.6	28	0.2	353.0	49.4	396	21.06	8.1	38.9	10.2	3	<0.1	0.3	0.3	275	0.05
STD OXK94	Standard		3598																		
STD OXK94	Standard		3507																		
STD SH55	Standard		1368																		
STD SH55	Standard		1360																		
STD SH55 Expected			1375																		
STD OXK94 Expected			3562																		
STD DS9 Expected				12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201
STD OREAS45EA Expected				1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	1.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1-WHI	Prep Blank		<2	<0.1	2.8	3.8	39	<0.1	2.5	3.9	541	1.83	1.5	1.4	5.7	52	<0.1	<0.1	<0.1	34	0.43
G1-WHI	Prep Blank		2																		
G1-WHI	Prep Blank			<0.1	3.1	3.5	44	<0.1	3.4	4.4	562	1.92	1.0	1.0	5.2	51	<0.1	<0.1	<0.1	35	0.44

## QUALITY CONTROL REPORT

WHI13000088.1

	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te
	Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
	MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
Pulp Duplicates																			
REP G1-WHI	QC	0.072	9	5	0.51	165	0.115	<20	0.92	0.074	0.49	<0.1	<0.01	0.3	<0.05	1.9	<0.5	4	<0.2
1243726	Rock	0.035	31	22	0.98	229	0.002	<20	1.92	0.006	0.16	0.6	<0.01	<0.1	0.05	2.3	<0.5	5	<0.2
REP 1243726	QC																		
Core Reject Duplicates																			
1243701	Rock	0.013	9	9	0.16	8	<0.001	<20	0.25	0.028	<0.01	<0.1	<0.01	<0.1	<0.05	1.1	<0.5	<1	<0.2
DUP 1243701	QC	0.011	8	9	0.17	8	<0.001	<20	0.27	0.035	<0.01	<0.1	<0.01	0.2	<0.05	1.3	<0.5	1	<0.2
Reference Materials																			
STD DS9	Standard	0.080	11	112	0.61	308	0.103	<20	0.92	0.078	0.39	2.8	0.16	4.7	0.16	2.0	4.0	4	5.0
STD OREAS45EA	Standard	0.028	6	791	0.09	144	0.084	<20	2.82	0.017	0.05	<0.1	0.01	<0.1	<0.05	74.1	1.1	11	<0.2
STD OXK94	Standard																		
STD OXK94	Standard																		
STD SH55	Standard																		
STD SH55	Standard																		
STD SH55 Expected																			
STD OXK94 Expected																			
STD DS9 Expected		0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59	5.02
STD OREAS45EA Expected		0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7	0.11
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.078	10	4	0.51	160	0.115	<20	0.92	0.080	0.48	<0.1	<0.01	0.3	<0.05	2.1	<0.5	5	<0.2
G1-WHI	Prep Blank																		
G1-WHI	Prep Blank	0.064	10	5	0.52	170	0.119	<20	0.93	0.077	0.50	<0.1	<0.01	0.3	<0.05	2.4	<0.5	4	<0.2