

Acme Analytical Laboratories (Vancouver) Ltd.  
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA  
PHONE (604) 253-3158

**Client:** **Goldstrike Resources Ltd.**  
1300 - 1111 West Georgia Street  
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List  
Receiving Lab: Canada-Whitehorse  
Received: July 12, 2013  
Report Date: August 23, 2013  
Page: 1 of 2

## CERTIFICATE OF ANALYSIS

WHI13000118.1

### CLIENT JOB INFORMATION

Project: Plateau South  
Shipment ID: PLAS\_CHANNEL\_2013\_3  
P.O. Number  
Number of Samples: 17

### SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days  
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.  
1300 - 1111 West Georgia Street  
Vancouver BC V6E 4M3  
CANADA

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

| Procedure Code | Number of Samples | Code Description                                  | Test Wgt (g) | Report Status | Lab |
|----------------|-------------------|---|--------------|---------------|-----|
| R200-250       | 17                | Crush, split and pulverize 250 g rock to 200 mesh |              |               | WHI |
| 3B             | 17                | Fire assay fusion Au by ICP-ES                    | 30           | Completed     | VAN |
| 1DX            | 17                | 1:1:1 Aqua Regia digestion ICP-MS analysis        | 0.5          | Completed     | VAN |

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.  
\*\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

# CERTIFICATE OF ANALYSIS

WHI13000118.1

|         | Method  | WGHT | 3B   | 1DX  | 1DX | 1DX  | 1DX | 1DX  | 1DX | 1DX | 1DX | 1DX  | 1DX    | 1DX   | 1DX  | 1DX | 1DX  | 1DX  | 1DX  | 1DX | 1DX  |
|---------|---------|------|------|------|-----|------|-----|------|-----|-----|-----|------|--------|-------|------|-----|------|------|------|-----|------|
|         | Analyte | Wgt  | Au   | Mo   | Cu  | Pb   | Zn  | Ag   | Ni  | Co  | Mn  | Fe   | As     | Au    | Th   | Sr  | Cd   | Sb   | Bi   | V   | Ca   |
|         | Unit    | kg   | ppb  | ppm  | ppm | ppm  | ppm | ppm  | ppm | ppm | ppm | %    | ppm    | ppb   | ppm  | ppm | ppm  | ppm  | ppm  | ppm | %    |
|         | MDL     | 0.01 | 2    | 0.1  | 0.1 | 0.1  | 1   | 0.1  | 0.1 | 0.1 | 1   | 0.01 | 0.5    | 0.5   | 0.1  | 1   | 0.1  | 0.1  | 0.1  | 2   | 0.01 |
| 1243747 | Rock    | 1.84 | 109  | 0.1  | 4.8 | 9.8  | 11  | 0.1  | 4.2 | 2.1 | 85  | 0.87 | 698.3  | 42.1  | 7.0  | 4   | <0.1 | 0.2  | 0.2  | 3   | 0.02 |
| 1243748 | Rock    | 2.37 | <2   | 0.1  | 6.3 | 8.2  | 16  | 0.1  | 7.2 | 3.3 | 123 | 0.98 | 24.0   | 113.8 | 7.5  | 5   | <0.1 | <0.1 | 0.2  | 4   | 0.12 |
| 1243749 | Rock    | 4.89 | <2   | 0.1  | 5.2 | 7.6  | 13  | <0.1 | 5.1 | 2.6 | 122 | 0.94 | 32.7   | 6.6   | 6.9  | 3   | <0.1 | <0.1 | <0.1 | 3   | 0.03 |
| 1243750 | Rock    | 1.06 | 559  | 0.1  | 4.2 | 4.3  | 9   | <0.1 | 2.6 | 1.1 | 77  | 0.59 | 133.1  | 115.2 | 3.8  | 2   | <0.1 | <0.1 | <0.1 | <2  | 0.01 |
| 1243751 | Rock    | 1.68 | 110  | 0.1  | 4.6 | 7.7  | 15  | <0.1 | 4.4 | 2.7 | 87  | 1.03 | 1059   | 80.6  | 8.3  | 3   | <0.1 | 0.3  | <0.1 | 4   | 0.03 |
| 1243752 | Rock    | 0.66 | 1878 | 0.2  | 3.0 | 47.6 | 6   | 0.8  | 2.2 | 1.3 | 46  | 4.07 | >10000 | 1784  | 6.8  | 2   | <0.1 | 14.0 | 0.4  | 2   | 0.01 |
| 1243753 | Rock    | 5.38 | 29   | 0.1  | 4.7 | 9.1  | 13  | <0.1 | 5.1 | 2.3 | 106 | 0.85 | 457.6  | 18.2  | 10.6 | 3   | <0.1 | 0.1  | <0.1 | 3   | 0.03 |
| 1243754 | Rock    | 1.16 | 31   | 0.1  | 8.0 | 7.8  | 19  | <0.1 | 7.1 | 3.4 | 105 | 1.32 | 672.1  | 19.3  | 14.5 | 4   | <0.1 | 0.2  | <0.1 | 4   | 0.04 |
| 1243755 | Rock    | 1.66 | 446  | 0.1  | 3.8 | 36.1 | 4   | 0.2  | 3.1 | 1.9 | 79  | 1.74 | >10000 | 529.2 | 8.5  | 4   | <0.1 | 3.1  | 0.1  | <2  | 0.02 |
| 1243756 | Rock    | 1.80 | 3    | <0.1 | 4.6 | 9.6  | 22  | <0.1 | 5.6 | 2.9 | 63  | 1.21 | 147.5  | 2.6   | 8.6  | 4   | <0.1 | <0.1 | <0.1 | 5   | 0.04 |
| 1243757 | Rock    | 2.01 | 4    | <0.1 | 3.2 | 9.2  | 19  | <0.1 | 5.4 | 2.8 | 88  | 1.14 | 185.0  | 1.4   | 8.7  | 4   | <0.1 | <0.1 | <0.1 | 4   | 0.04 |
| 1243758 | Rock    | 1.96 | 17   | <0.1 | 5.0 | 7.9  | 14  | <0.1 | 5.4 | 2.8 | 109 | 0.87 | 356.9  | 15.0  | 5.9  | 3   | <0.1 | 0.1  | <0.1 | 3   | 0.02 |
| 1243759 | Rock    | 0.69 | 3892 | 0.2  | 3.6 | 17.5 | 13  | 0.4  | 7.2 | 5.3 | 89  | 3.19 | >10000 | 2254  | 5.7  | 4   | <0.1 | 6.1  | 0.1  | 3   | 0.02 |
| 1243760 | Rock    | 1.52 | 152  | <0.1 | 4.2 | 9.1  | 17  | <0.1 | 5.6 | 2.8 | 105 | 0.99 | 1373   | 170.5 | 5.3  | 3   | <0.1 | 0.3  | <0.1 | 2   | 0.03 |
| 1243761 | Rock    | 0.75 | 5    | <0.1 | 3.7 | 7.3  | 22  | <0.1 | 5.5 | 4.1 | 145 | 0.93 | 108.7  | 3.4   | 6.2  | 5   | <0.1 | <0.1 | <0.1 | 3   | 0.15 |
| 1243762 | Rock    | 1.60 | 4595 | 0.2  | 2.4 | 30.7 | 6   | 0.8  | 4.7 | 2.8 | 62  | 2.62 | >10000 | 3781  | 5.3  | 4   | <0.1 | 5.8  | 0.2  | <2  | 0.02 |
| 1243763 | Rock    | 3.03 | 193  | 0.1  | 2.3 | 9.5  | 13  | <0.1 | 5.6 | 3.2 | 117 | 0.95 | 3858   | 218.4 | 6.4  | 4   | <0.1 | 0.9  | <0.1 | 2   | 0.03 |

# CERTIFICATE OF ANALYSIS

WHI13000118.1

|         | Method  | 1DX   | 1DX | 1DX | 1DX  | 1DX | 1DX    | 1DX | 1DX  | 1DX   | 1DX  | 1DX  | 1DX   | 1DX  | 1DX   | 1DX | 1DX  | 1DX |
|---------|---------|-------|-----|-----|------|-----|--------|-----|------|-------|------|------|-------|------|-------|-----|------|-----|
|         | Analyte | P     | La  | Cr  | Mg   | Ba  | Ti     | B   | Al   | Na    | K    | W    | Hg    | Tl   | S     | Sc  | Se   | Ga  |
|         | Unit    | %     | ppm | ppm | %    | ppm | %      | ppm | %    | %     | %    | ppm  | ppm   | ppm  | %     | ppm | ppm  | ppm |
|         | MDL     | 0.001 | 1   | 1   | 0.01 | 1   | 0.001  | 20  | 0.01 | 0.001 | 0.01 | 0.1  | 0.01  | 0.1  | 0.05  | 0.1 | 0.5  | 1   |
| 1243747 | Rock    | 0.012 | 11  | 7   | 0.10 | 84  | <0.001 | <20 | 0.26 | 0.015 | 0.06 | 0.1  | <0.01 | <0.1 | <0.05 | 0.5 | <0.5 | <1  |
| 1243748 | Rock    | 0.019 | 12  | 8   | 0.16 | 38  | 0.001  | <20 | 0.37 | 0.024 | 0.07 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | 1   |
| 1243749 | Rock    | 0.015 | 12  | 5   | 0.14 | 27  | <0.001 | <20 | 0.33 | 0.021 | 0.07 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | 1   |
| 1243750 | Rock    | 0.007 | 7   | 5   | 0.04 | 20  | <0.001 | <20 | 0.13 | 0.015 | 0.04 | <0.1 | <0.01 | <0.1 | <0.05 | 0.5 | <0.5 | <1  |
| 1243751 | Rock    | 0.017 | 14  | 8   | 0.14 | 31  | <0.001 | <20 | 0.35 | 0.022 | 0.07 | <0.1 | <0.01 | <0.1 | <0.05 | 0.5 | <0.5 | 1   |
| 1243752 | Rock    | 0.013 | 8   | 6   | 0.04 | 23  | <0.001 | <20 | 0.17 | 0.015 | 0.06 | <0.1 | <0.01 | <0.1 | 1.06  | 0.5 | 1.0  | <1  |
| 1243753 | Rock    | 0.018 | 17  | 8   | 0.09 | 32  | <0.001 | <20 | 0.29 | 0.028 | 0.07 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | <1  |
| 1243754 | Rock    | 0.022 | 21  | 8   | 0.19 | 28  | <0.001 | <20 | 0.47 | 0.020 | 0.10 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | 2   |
| 1243755 | Rock    | 0.010 | 11  | 5   | 0.03 | 29  | <0.001 | <20 | 0.15 | 0.017 | 0.06 | <0.1 | <0.01 | <0.1 | 0.23  | 0.7 | <0.5 | <1  |
| 1243756 | Rock    | 0.020 | 17  | 9   | 0.24 | 19  | 0.001  | <20 | 0.56 | 0.026 | 0.08 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | 2   |
| 1243757 | Rock    | 0.023 | 15  | 10  | 0.21 | 18  | 0.001  | <20 | 0.50 | 0.025 | 0.07 | <0.1 | <0.01 | <0.1 | <0.05 | 0.6 | <0.5 | 2   |
| 1243758 | Rock    | 0.014 | 9   | 6   | 0.12 | 17  | <0.001 | <20 | 0.30 | 0.018 | 0.05 | <0.1 | <0.01 | <0.1 | <0.05 | 0.5 | <0.5 | 1   |
| 1243759 | Rock    | 0.014 | 6   | 6   | 0.10 | 27  | <0.001 | <20 | 0.27 | 0.017 | 0.06 | <0.1 | <0.01 | <0.1 | 1.22  | 0.4 | 0.6  | <1  |
| 1243760 | Rock    | 0.012 | 9   | 7   | 0.10 | 29  | <0.001 | <20 | 0.28 | 0.019 | 0.05 | <0.1 | <0.01 | <0.1 | 0.06  | 0.6 | <0.5 | <1  |
| 1243761 | Rock    | 0.015 | 10  | 7   | 0.14 | 32  | <0.001 | <20 | 0.35 | 0.019 | 0.06 | <0.1 | <0.01 | <0.1 | <0.05 | 0.5 | <0.5 | 1   |
| 1243762 | Rock    | 0.014 | 6   | 4   | 0.04 | 24  | <0.001 | <20 | 0.17 | 0.015 | 0.05 | <0.1 | <0.01 | <0.1 | 0.83  | 0.4 | <0.5 | <1  |
| 1243763 | Rock    | 0.016 | 10  | 6   | 0.06 | 25  | <0.001 | <20 | 0.23 | 0.023 | 0.06 | <0.1 | <0.01 | <0.1 | 0.14  | 0.5 | <0.5 | <1  |

## QUALITY CONTROL REPORT

WHI13000118.1

|                        | Method     | WGHT | 3B   | 1DX   | 1DX   | 1DX   | 1DX  | 1DX   | 1DX   | 1DX  | 1DX | 1DX   | 1DX  | 1DX   | 1DX  | 1DX  | 1DX  | 1DX  | 1DX  | 1DX | 1DX    |
|------------------------|------------|------|------|-------|-------|-------|------|-------|-------|------|-----|-------|------|-------|------|------|------|------|------|-----|--------|
|                        | Analyte    | Wgt  | Au   | Mo    | Cu    | Pb    | Zn   | Ag    | Ni    | Co   | Mn  | Fe    | As   | Au    | Th   | Sr   | Cd   | Sb   | Bi   | V   | Ca     |
|                        | Unit       | kg   | ppb  | ppm   | ppm   | ppm   | ppm  | ppm   | ppm   | ppm  | ppm | %     | ppm  | ppb   | ppm  | ppm  | ppm  | ppm  | ppm  | ppm | %      |
|                        | MDL        | 0.01 | 2    | 0.1   | 0.1   | 0.1   | 1    | 0.1   | 0.1   | 0.1  | 1   | 0.01  | 0.5  | 0.5   | 0.1  | 1    | 0.1  | 0.1  | 0.1  | 2   | 0.01   |
| Pulp Duplicates        |            |      |      |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| 1243749                | Rock       | 4.89 | <2   | 0.1   | 5.2   | 7.6   | 13   | <0.1  | 5.1   | 2.6  | 122 | 0.94  | 32.7 | 6.6   | 6.9  | 3    | <0.1 | <0.1 | <0.1 | 3   | 0.03   |
| REP 1243749            | QC         |      |      | <0.1  | 5.1   | 7.3   | 14   | <0.1  | 4.7   | 2.4  | 119 | 0.91  | 31.2 | 4.2   | 6.8  | 3    | <0.1 | <0.1 | <0.1 | 3   | 0.03   |
| 1243751                | Rock       | 1.68 | 110  | 0.1   | 4.6   | 7.7   | 15   | <0.1  | 4.4   | 2.7  | 87  | 1.03  | 1059 | 80.6  | 8.3  | 3    | <0.1 | 0.3  | <0.1 | 4   | 0.03   |
| REP 1243751            | QC         |      | 95   |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| Core Reject Duplicates |            |      |      |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| 1243763                | Rock       | 3.03 | 193  | 0.1   | 2.3   | 9.5   | 13   | <0.1  | 5.6   | 3.2  | 117 | 0.95  | 3858 | 218.4 | 6.4  | 4    | <0.1 | 0.9  | <0.1 | 2   | 0.03   |
| DUP 1243763            | QC         |      | 196  | 0.1   | 2.3   | 9.2   | 12   | <0.1  | 5.5   | 3.0  | 115 | 0.89  | 3242 | 322.6 | 6.6  | 4    | <0.1 | 0.7  | <0.1 | 2   | 0.03   |
| Reference Materials    |            |      |      |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| STD DS9                | Standard   |      |      | 14.3  | 107.3 | 121.4 | 305  | 1.7   | 39.4  | 7.8  | 612 | 2.48  | 25.4 | 115.6 | 6.1  | 60   | 2.3  | 4.0  | 6.0  | 42  | 0.71   |
| STD OREAS45EA          | Standard   |      |      | 1.4   | 683.2 | 13.3  | 28   | 0.3   | 380.8 | 52.5 | 395 | 23.53 | 7.8  | 62.8  | 9.3  | 3    | <0.1 | 0.1  | 0.3  | 299 | 0.03   |
| STD OXK94              | Standard   |      | 3578 |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| STD SH55               | Standard   |      | 1385 |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| STD SH55 Expected      |            |      | 1375 |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| STD OXK94 Expected     |            |      | 3562 |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| STD DS9 Expected       |            |      |      | 12.84 | 108   | 126   | 317  | 1.83  | 40.3  | 7.6  | 575 | 2.33  | 25.5 | 118   | 6.38 | 69.6 | 2.4  | 4.94 | 6.32 | 40  | 0.7201 |
| STD OREAS45EA Expected |            |      |      | 1.78  | 709   | 14.3  | 30.6 | 0.311 | 357   | 52   | 400 | 22.65 | 11.4 | 53    | 10.7 | 4.05 | 0.03 | 0.64 | 0.26 | 295 | 0.032  |
| BLK                    | Blank      |      | <2   |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| BLK                    | Blank      |      | <2   |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| BLK                    | Blank      |      |      | <0.1  | <0.1  | <0.1  | <1   | <0.1  | <0.1  | <0.1 | <1  | <0.01 | 1.4  | <0.5  | <0.1 | <1   | <0.1 | <0.1 | <0.1 | <2  | <0.01  |
| Prep Wash              |            |      |      |       |       |       |      |       |       |      |     |       |      |       |      |      |      |      |      |     |        |
| G1-WHI                 | Prep Blank |      | <2   | 0.2   | 26.9  | 4.0   | 48   | 0.2   | 2.9   | 4.3  | 555 | 1.98  | <0.5 | 1.1   | 5.6  | 48   | <0.1 | <0.1 | 0.3  | 39  | 0.52   |
| G1-WHI                 | Prep Blank |      | <2   | 0.1   | 6.1   | 3.3   | 45   | <0.1  | 2.6   | 4.1  | 528 | 1.87  | <0.5 | <0.5  | 5.3  | 42   | <0.1 | <0.1 | 0.2  | 36  | 0.46   |

## QUALITY CONTROL REPORT

WHI13000118.1

|                        | Method     | 1DX    | 1DX  | 1DX | 1DX    | 1DX | 1DX    | 1DX | 1DX    | 1DX    | 1DX   | 1DX  | 1DX   | 1DX   | 1DX    | 1DX  | 1DX  | 1DX  | 1DX  |
|------------------------|------------|--------|------|-----|--------|-----|--------|-----|--------|--------|-------|------|-------|-------|--------|------|------|------|------|
|                        | Analyte    | P      | La   | Cr  | Mg     | Ba  | Ti     | B   | Al     | Na     | K     | W    | Hg    | Tl    | S      | Sc   | Se   | Ga   | Te   |
|                        | Unit       | %      | ppm  | ppm | %      | ppm | %      | ppm | %      | %      | %     | ppm  | ppm   | ppm   | %      | ppm  | ppm  | ppm  | ppm  |
|                        | MDL        | 0.001  | 1    | 1   | 0.01   | 1   | 0.001  | 20  | 0.01   | 0.001  | 0.01  | 0.1  | 0.01  | 0.1   | 0.05   | 0.1  | 0.5  | 1    | 0.2  |
| Pulp Duplicates        |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| 1243749                | Rock       | 0.015  | 12   | 5   | 0.14   | 27  | <0.001 | <20 | 0.33   | 0.021  | 0.07  | <0.1 | <0.01 | <0.1  | <0.05  | 0.6  | <0.5 | 1    | <0.2 |
| REP 1243749            | QC         | 0.016  | 13   | 7   | 0.13   | 28  | <0.001 | <20 | 0.35   | 0.022  | 0.07  | <0.1 | <0.01 | <0.1  | <0.05  | 0.6  | <0.5 | 1    | <0.2 |
| 1243751                | Rock       | 0.017  | 14   | 8   | 0.14   | 31  | <0.001 | <20 | 0.35   | 0.022  | 0.07  | <0.1 | <0.01 | <0.1  | <0.05  | 0.5  | <0.5 | 1    | <0.2 |
| REP 1243751            | QC         |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| Core Reject Duplicates |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| 1243763                | Rock       | 0.016  | 10   | 6   | 0.06   | 25  | <0.001 | <20 | 0.23   | 0.023  | 0.06  | <0.1 | <0.01 | <0.1  | 0.14   | 0.5  | <0.5 | <1   | <0.2 |
| DUP 1243763            | QC         | 0.017  | 10   | 7   | 0.06   | 24  | <0.001 | <20 | 0.24   | 0.024  | 0.06  | <0.1 | <0.01 | <0.1  | 0.12   | 0.5  | <0.5 | <1   | <0.2 |
| Reference Materials    |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| STD DS9                | Standard   | 0.076  | 14   | 123 | 0.62   | 288 | 0.114  | <20 | 0.91   | 0.086  | 0.42  | 2.5  | 0.18  | 5.2   | 0.17   | 2.5  | 4.8  | 5    | 5.1  |
| STD OREAS45EA          | Standard   | 0.027  | 6    | 937 | 0.09   | 137 | 0.088  | <20 | 3.03   | 0.025  | 0.05  | <0.1 | <0.01 | <0.1  | <0.05  | 70.3 | 0.6  | 11   | <0.2 |
| STD OXK94              | Standard   |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| STD SH55               | Standard   |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| STD SH55 Expected      |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| STD OXK94 Expected     |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| STD DS9 Expected       |            | 0.0819 | 13.3 | 121 | 0.6165 | 330 | 0.1108 |     | 0.9577 | 0.0853 | 0.395 | 2.89 | 0.2   | 5.3   | 0.1615 | 2.5  | 5.2  | 4.59 | 5.02 |
| STD OREAS45EA Expected |            | 0.029  | 8.19 | 849 | 0.095  | 148 | 0.106  |     | 3.32   | 0.027  | 0.053 |      | 0.34  | 0.072 | 0.044  | 78   | 2.09 | 11.7 | 0.11 |
| BLK                    | Blank      |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| BLK                    | Blank      |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| BLK                    | Blank      | <0.001 | <1   | <1  | <0.01  | <1  | <0.001 | <20 | <0.01  | <0.001 | <0.01 | <0.1 | <0.01 | <0.1  | <0.05  | <0.1 | <0.5 | <1   | <0.2 |
| Prep Wash              |            |        |      |     |        |     |        |     |        |        |       |      |       |       |        |      |      |      |      |
| G1-WHI                 | Prep Blank | 0.077  | 12   | 7   | 0.54   | 398 | 0.119  | <20 | 0.89   | 0.069  | 0.47  | 0.1  | <0.01 | 0.3   | <0.05  | 2.3  | <0.5 | 4    | <0.2 |
| G1-WHI                 | Prep Blank | 0.069  | 11   | 6   | 0.51   | 203 | 0.117  | <20 | 0.88   | 0.069  | 0.49  | 0.1  | <0.01 | 0.3   | <0.05  | 2.2  | <0.5 | 4    | <0.2 |