

Acme Analytical Laboratories (Vancouver) Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List
Receiving Lab: Canada-Whitehorse
Received: June 27, 2013
Report Date: August 23, 2013
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI13000066.1

CLIENT JOB INFORMATION

Project: Plateau South
Shipment ID: PLAS_ROCK_2013_2
P.O. Number
Number of Samples: 46

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3
CANADA

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	46	Crush, split and pulverize 250 g rock to 200 mesh			WHI
3B	46	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1DX	46	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

CERTIFICATE OF ANALYSIS

WHI13000066.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1237452	Rock	1.79	5	3.3	27.1	16.8	66	<0.1	30.0	13.7	297	3.68	19.2	3.7	8.6	6	<0.1	<0.1	0.8	22
1237453	Rock	0.73	4	0.2	90.6	7.3	50	0.2	36.9	54.6	316	4.94	3.4	3.2	11.1	590	<0.1	<0.1	0.8	50
1237454	Rock	0.81	7	1.1	357.1	9.1	47	0.7	90.1	27.1	146	6.77	<0.5	4.8	16.7	142	0.1	<0.1	1.0	54
1237455	Rock	0.69	<2	0.7	41.6	22.8	37	0.2	17.1	4.7	134	2.46	3.8	2.5	8.4	8	<0.1	<0.1	0.5	35
1237456	Rock	0.82	<2	0.6	169.1	8.1	66	0.1	18.1	7.8	48	1.47	5.3	<0.5	18.2	145	0.2	<0.1	0.2	16
1237457	Rock	1.26	<2	1.0	56.2	9.2	103	0.1	22.3	12.3	260	5.30	7.5	2.5	7.3	26	<0.1	<0.1	0.3	18
1237458	Rock	0.63	62	<0.1	20.8	10.2	24	<0.1	21.5	6.9	149	1.40	278.1	55.2	7.2	18	<0.1	<0.1	0.4	13
1237459	Rock	0.78	<2	0.1	19.0	9.2	36	<0.1	9.2	3.9	253	1.98	15.4	<0.5	8.8	8	<0.1	<0.1	<0.1	15
1237461	Rock	0.48	7	0.1	52.1	8.7	30	<0.1	9.7	5.5	251	2.13	1.6	1.4	4.6	10	<0.1	<0.1	0.2	8
1237462	Rock	0.59	5	0.1	31.7	31.3	46	<0.1	20.9	8.9	521	1.86	40.5	5.1	8.1	13	0.2	0.2	0.2	3
1237463	Rock	0.62	85	0.1	11.6	12.8	44	<0.1	14.5	5.7	315	1.69	34.2	29.9	5.5	3	<0.1	<0.1	<0.1	4
1237464	Rock	0.68	78	<0.1	15.1	10.6	7	<0.1	3.8	1.9	214	0.79	12.4	21.7	2.8	4	<0.1	<0.1	<0.1	<2
1237465	Rock	0.44	<2	<0.1	5.2	2.5	26	<0.1	6.7	1.4	140	0.84	3.5	<0.5	2.3	2	<0.1	0.8	<0.1	<2
1237466	Rock	0.69	3	0.1	34.6	4.0	45	<0.1	13.9	5.3	210	2.28	82.8	2.1	8.2	9	0.1	0.6	<0.1	9
1237467	Rock	0.62	<2	0.1	1.2	8.8	2	<0.1	1.3	0.6	97	0.45	2.2	0.6	0.2	11	<0.1	<0.1	<0.1	<2
1237469	Rock	0.57	<2	<0.1	1.4	4.7	7	<0.1	0.6	0.5	116	0.55	2.4	<0.5	0.7	473	<0.1	0.2	<0.1	<2
1237471	Rock	0.63	167	0.5	34.9	88.7	41	0.5	4.5	1.7	99	1.89	237.9	165.8	4.2	19	0.2	0.3	2.3	<2
1243901	Rock	1.33	10	0.6	10.6	9.5	16	<0.1	6.5	1.9	100	1.04	88.9	15.2	5.6	3	<0.1	0.2	0.4	3
1243902	Rock	1.49	25	0.2	10.5	4.1	10	<0.1	1.3	0.5	63	1.31	164.6	36.4	2.8	4	<0.1	<0.1	0.4	<2
1243903	Rock	1.28	34	0.2	13.5	11.2	31	<0.1	21.1	4.9	117	1.51	490.9	36.8	11.2	8	0.3	0.3	0.6	6
1243904	Rock	2.28	52	<0.1	8.3	12.4	12	0.1	6.5	2.3	263	1.00	543.9	55.0	4.0	5	<0.1	0.2	1.8	<2
1243905	Rock	0.69	37	0.2	9.8	6.6	28	<0.1	13.4	8.6	521	1.58	230.9	38.6	7.2	2	0.3	0.3	0.1	3
1243906	Rock	1.60	<2	0.1	3.7	5.8	19	<0.1	3.6	1.3	113	0.95	21.6	1.0	1.4	4	<0.1	0.4	0.2	<2
1243907	Rock	2.38	76	0.1	3.2	2.8	4	<0.1	2.8	0.7	46	0.58	614.1	89.0	0.2	<1	0.1	0.2	<0.1	<2
1243908	Rock	0.99	98	0.2	12.3	1.9	13	<0.1	9.5	3.9	117	1.32	1274	31.1	1.4	3	<0.1	0.3	<0.1	<2
1243909	Rock	1.81	911	0.1	11.8	10.3	23	<0.1	6.0	2.2	353	1.52	998.5	879.2	1.6	4	0.1	0.2	0.2	3
1243910	Rock	1.61	<2	0.1	10.9	9.6	33	<0.1	9.8	3.8	434	1.21	4.1	<0.5	6.5	10	0.1	<0.1	<0.1	6
1243911	Rock	1.90	152	<0.1	19.7	6.2	27	<0.1	13.9	7.0	337	1.83	1222	100.3	7.6	8	<0.1	0.2	<0.1	3
1243912	Rock	1.66	38	0.5	73.3	2.7	40	0.2	25.2	11.1	65	1.83	116.4	39.0	30.7	18	0.1	<0.1	1.2	82
1243913	Rock	1.93	7	19.8	440.7	11.8	118	0.4	97.8	117.8	466	6.21	4.1	9.9	9.1	8	<0.1	0.2	0.7	105

Acme Analytical Laboratories (Vancouver) Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Project: Plateau South
Report Date: August 23, 2013

Page: 2 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI13000066.1

	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga
	Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm
	MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1
1237452	Rock	0.012	16	28	0.71	54	0.098	<20	1.96	0.023	0.62	<0.1	<0.01	0.4	<0.05	2.2	<0.5	5
1237453	Rock	0.037	7	47	2.28	99	0.220	<20	6.03	0.356	2.19	0.1	<0.01	1.0	1.56	9.6	<0.5	15
1237454	Rock	0.062	39	95	0.78	24	0.154	<20	4.97	0.449	0.44	0.3	<0.01	0.2	3.49	5.7	1.6	15
1237455	Rock	0.006	14	33	0.57	58	0.021	<20	0.90	0.028	0.44	<0.1	<0.01	0.2	1.10	2.2	<0.5	4
1237456	Rock	0.031	28	18	0.29	14	0.107	<20	1.10	0.015	0.20	2.2	<0.01	<0.1	0.36	1.3	<0.5	4
1237457	Rock	0.008	16	16	0.74	32	0.039	<20	1.72	0.047	0.42	<0.1	<0.01	0.2	2.21	5.5	<0.5	6
1237458	Rock	0.012	8	15	0.20	17	0.043	<20	0.54	0.051	0.06	0.3	<0.01	<0.1	0.27	1.2	<0.5	2
1237459	Rock	0.009	13	20	0.35	127	0.033	<20	0.84	0.034	0.19	0.1	<0.01	<0.1	<0.05	1.6	<0.5	3
1237461	Rock	0.015	7	12	0.35	34	0.015	<20	0.79	0.026	0.12	<0.1	<0.01	<0.1	0.15	1.1	<0.5	2
1237462	Rock	0.002	13	7	0.12	455	0.002	<20	0.39	0.037	0.06	0.6	<0.01	<0.1	0.13	2.3	<0.5	<1
1237463	Rock	0.005	13	6	0.16	119	0.002	<20	0.49	0.032	0.09	0.2	<0.01	<0.1	<0.05	1.7	<0.5	1
1237464	Rock	0.002	5	3	0.03	82	0.003	<20	0.16	0.005	0.04	0.3	<0.01	<0.1	<0.05	0.3	<0.5	<1
1237465	Rock	0.004	5	5	0.06	29	0.001	<20	0.18	0.014	0.04	<0.1	<0.01	<0.1	<0.05	0.4	<0.5	<1
1237466	Rock	0.023	13	19	0.41	176	0.009	<20	0.84	0.040	0.04	0.4	<0.01	<0.1	<0.05	4.3	<0.5	2
1237467	Rock	0.001	1	2	0.02	4	<0.001	<20	0.03	0.003	<0.01	<0.1	<0.01	<0.1	<0.05	0.2	<0.5	<1
1237469	Rock	0.008	4	<1	0.10	11	<0.001	<20	0.04	0.001	0.02	<0.1	<0.01	<0.1	<0.05	0.5	<0.5	<1
1237471	Rock	0.018	8	6	0.03	28	<0.001	<20	0.29	0.007	0.11	<0.1	<0.01	<0.1	0.22	0.4	<0.5	<1
1243901	Rock	0.008	11	8	0.04	29	0.001	<20	0.26	0.024	0.07	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1
1243902	Rock	0.007	4	4	0.02	23	<0.001	<20	0.18	0.016	0.05	<0.1	<0.01	<0.1	<0.05	0.8	<0.5	<1
1243903	Rock	0.041	25	13	0.09	39	0.002	<20	0.35	0.025	0.06	1.3	<0.01	<0.1	<0.05	1.2	<0.5	<1
1243904	Rock	0.020	8	3	0.04	63	0.001	<20	0.27	0.022	0.09	<0.1	<0.01	<0.1	0.07	0.8	<0.5	<1
1243905	Rock	0.012	18	4	0.02	43	<0.001	<20	0.32	0.003	0.15	0.4	<0.01	<0.1	<0.05	1.2	<0.5	<1
1243906	Rock	0.020	3	20	0.08	15	0.001	<20	0.22	0.011	0.03	<0.1	<0.01	<0.1	<0.05	0.6	<0.5	<1
1243907	Rock	0.004	<1	20	<0.01	60	<0.001	<20	0.05	0.002	<0.01	0.2	<0.01	<0.1	<0.05	0.2	<0.5	<1
1243908	Rock	0.009	4	23	0.04	40	<0.001	<20	0.17	0.006	0.05	<0.1	<0.01	<0.1	<0.05	0.4	<0.5	<1
1243909	Rock	0.014	3	22	0.18	37	0.002	<20	0.34	0.023	0.02	2.2	<0.01	<0.1	<0.05	0.7	<0.5	<1
1243910	Rock	0.005	13	20	0.26	53	0.012	<20	0.43	0.030	0.08	<0.1	<0.01	<0.1	<0.05	1.1	<0.5	2
1243911	Rock	0.013	11	15	0.13	181	0.001	<20	0.42	0.021	0.10	0.3	<0.01	<0.1	0.11	1.3	<0.5	<1
1243912	Rock	0.006	36	59	0.35	83	0.084	<20	1.02	0.026	0.65	0.1	<0.01	0.3	0.37	10.5	<0.5	7
1243913	Rock	0.046	20	69	0.85	38	0.241	<20	2.28	0.033	1.49	0.2	<0.01	0.8	2.53	8.6	<0.5	10

CERTIFICATE OF ANALYSIS

WHI13000066.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1243914	Rock	0.54	2	0.5	55.0	12.1	32	0.1	23.3	8.7	219	2.56	23.4	2.5	4.4	14	<0.1	<0.1	0.2	21
1243915	Rock	0.79	59	1.0	76.9	5.7	29	0.1	7.6	4.3	393	3.33	6.8	24.9	1.4	13	<0.1	<0.1	2.5	9
1243916	Rock	1.03	<2	0.1	1.0	10.2	116	<0.1	53.6	21.9	232	6.12	<0.5	<0.5	15.2	26	<0.1	<0.1	0.2	81
1243917	Rock	1.60	<2	0.1	5.9	11.3	59	<0.1	28.2	11.3	157	4.05	17.1	1.8	12.0	29	<0.1	1.1	<0.1	35
1243918	Rock	1.73	4	1.7	30.0	35.3	40	0.1	26.6	12.8	250	4.56	3.2	4.2	11.2	8	<0.1	0.1	1.2	24
1243928	Rock	1.92	<2	<0.1	4.2	14.4	15	<0.1	1.6	0.7	436	0.83	11.8	<0.5	3.8	3	0.2	<0.1	<0.1	<2
1247951	Rock	0.80	<2	6.9	27.5	12.6	16	0.1	25.9	11.0	142	2.53	2.5	1.4	9.5	117	0.2	<0.1	0.5	11
1247952	Rock	1.34	64	0.1	27.6	9.6	16	<0.1	11.1	6.3	45	1.05	613.6	206.3	9.7	4	0.2	0.3	<0.1	7
1247954	Rock	1.04	<2	0.5	12.3	15.0	15	<0.1	10.8	6.5	156	1.27	7.5	2.2	5.3	138	<0.1	0.1	0.3	11
1247955	Rock	0.87	307	0.1	28.8	4.5	21	<0.1	17.3	10.2	358	1.63	4.3	235.3	3.0	223	<0.1	<0.1	6.9	7
1247956	Rock	0.87	2	0.2	29.3	17.6	18	0.1	29.4	14.6	119	1.90	10.6	3.9	12.8	277	<0.1	<0.1	0.7	24
1247957	Rock	1.05	<2	0.3	13.0	4.3	25	<0.1	10.6	3.6	355	1.11	2.7	3.6	2.1	25	<0.1	<0.1	0.2	9
1247958	Rock	0.89	130	<0.1	9.8	68.4	29	0.7	6.8	2.7	378	1.24	1572	143.2	4.1	3	0.1	0.5	1.5	<2
1247960	Rock	1.00	161	0.2	19.4	4.3	23	<0.1	12.6	5.5	259	1.85	217.0	286.1	3.2	95	<0.1	0.2	1.4	10
1241351	Rock	0.83	79	<0.1	3.3	278.9	3	0.9	2.5	1.0	62	0.45	30.5	233.9	0.1	6	<0.1	0.1	3.6	<2
1241352	Rock	1.32	302	0.1	10.6	16.3	19	<0.1	11.2	4.6	585	1.52	6276	239.6	4.8	5	<0.1	0.9	0.4	<2

Acme Analytical Laboratories (Vancouver) Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**

1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Project: Plateau South

Report Date: August 23, 2013

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI13000066.1

	Method Analyte Unit MDL	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1
1243914	Rock	0.024	15	30	0.47	80	0.019	<20	1.21	0.030	0.33	<0.1	<0.01	0.2	0.73	1.6	<0.5	4
1243915	Rock	0.008	4	11	0.49	44	0.019	<20	0.56	0.002	0.03	<0.1	<0.01	<0.1	0.18	1.1	<0.5	1
1243916	Rock	0.027	43	84	1.14	185	0.035	<20	2.20	0.017	0.57	<0.1	<0.01	0.2	<0.05	4.6	<0.5	8
1243917	Rock	0.034	23	32	0.63	401	0.034	<20	1.85	0.006	0.35	0.1	<0.01	0.2	0.24	4.7	<0.5	7
1243918	Rock	0.013	19	32	0.35	68	0.055	<20	0.81	0.047	0.32	0.1	<0.01	0.1	0.86	2.7	<0.5	4
1243928	Rock	0.010	7	14	0.03	58	<0.001	<20	0.15	0.027	0.01	<0.1	<0.01	<0.1	<0.05	0.8	<0.5	<1
1247951	Rock	0.042	10	21	0.41	16	0.101	<20	2.02	0.060	0.17	0.4	<0.01	<0.1	1.07	1.0	0.9	5
1247952	Rock	0.005	14	24	0.12	92	0.003	<20	0.32	0.039	0.03	0.1	<0.01	<0.1	0.20	1.1	<0.5	<1
1247954	Rock	0.451	9	15	0.30	60	0.032	<20	0.61	0.039	0.17	0.3	<0.01	<0.1	0.33	1.5	<0.5	2
1247955	Rock	0.016	8	13	0.28	42	0.039	<20	1.26	0.060	0.05	0.2	<0.01	<0.1	0.48	1.1	<0.5	3
1247956	Rock	0.037	16	37	0.43	15	0.118	<20	3.87	0.383	0.28	0.5	<0.01	<0.1	0.75	3.3	<0.5	11
1247957	Rock	0.012	5	15	0.36	73	0.048	<20	0.58	0.007	0.08	0.2	<0.01	<0.1	0.26	1.0	<0.5	2
1247958	Rock	0.002	7	14	0.05	67	<0.001	<20	0.18	0.040	0.04	0.9	<0.01	<0.1	0.06	1.4	<0.5	<1
1247960	Rock	0.015	7	19	0.44	19	0.023	<20	1.24	0.062	0.09	<0.1	<0.01	<0.1	0.34	1.5	0.6	2
1241351	Rock	0.024	<1	13	0.03	3	<0.001	<20	0.07	0.006	<0.01	<0.1	<0.01	<0.1	<0.05	0.2	<0.5	<1
1241352	Rock	0.004	7	14	0.02	137	0.001	<20	0.21	0.026	0.05	0.2	<0.01	<0.1	0.32	0.9	<0.5	<1

QUALITY CONTROL REPORT

WHI13000066.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
Pulp Duplicates																					
1243901	Rock	1.33	10	0.6	10.6	9.5	16	<0.1	6.5	1.9	100	1.04	88.9	15.2	5.6	3	<0.1	0.2	0.4	3	0.04
REP 1243901	QC			0.5	10.9	9.8	16	<0.1	7.2	2.0	98	1.02	92.2	6.4	5.8	3	<0.1	0.2	0.3	3	0.04
1243913	Rock	1.93	7	19.8	440.7	11.8	118	0.4	97.8	117.8	466	6.21	4.1	9.9	9.1	8	<0.1	0.2	0.7	105	0.13
REP 1243913	QC		6																		
REP 1247957	QC			0.2	13.1	4.4	24	<0.1	11.6	3.9	373	1.16	2.3	1.6	2.2	24	<0.1	<0.1	0.1	10	0.14
Core Reject Duplicates																					
1237459	Rock	0.78	<2	0.1	19.0	9.2	36	<0.1	9.2	3.9	253	1.98	15.4	<0.5	8.8	8	<0.1	<0.1	<0.1	15	0.05
DUP 1237459	QC		4	0.1	19.1	9.2	36	<0.1	10.1	3.9	244	1.92	15.4	<0.5	8.6	8	<0.1	<0.1	<0.1	15	0.05
1247957	Rock	1.05	<2	0.3	13.0	4.3	25	<0.1	10.6	3.6	355	1.11	2.7	3.6	2.1	25	<0.1	<0.1	0.2	9	0.14
DUP 1247957	QC		<2	0.3	12.6	4.3	24	<0.1	11.1	4.0	364	1.12	1.9	2.1	2.2	24	<0.1	<0.1	0.2	9	0.14
Reference Materials																					
STD DS9	Standard			12.8	110.2	132.0	335	1.8	40.2	7.9	589	2.47	26.7	124.5	6.3	76	2.4	4.5	6.5	40	0.72
STD DS9	Standard			13.4	113.7	143.5	313	1.7	42.2	8.3	599	2.53	27.5	113.3	6.8	76	2.3	4.5	7.3	40	0.73
STD OREAS45EA	Standard			1.6	725.2	15.5	30	0.3	399.7	56.8	435	23.40	9.3	59.3	10.6	4	<0.1	0.1	0.2	333	0.04
STD OREAS45EA	Standard			1.4	716.5	14.5	31	0.2	395.4	54.0	430	23.11	9.3	44.1	10.3	4	<0.1	0.1	0.3	330	0.03
STD OXK94	Standard		3655																		
STD OXK94	Standard		3675																		
STD SH55	Standard		1448																		
STD SH55	Standard		1406																		
STD SH55 Expected			1375																		
STD OXK94 Expected			3562																		
STD DS9 Expected				12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201
STD OREAS45EA Expected				1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		4																		
BLK	Blank		<2																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01

QUALITY CONTROL REPORT

WHI13000066.1

Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
Pulp Duplicates																		
1243901 Rock	0.008	11	8	0.04	29	0.001	<20	0.26	0.024	0.07	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1	<0.2
REP 1243901 QC	0.008	11	8	0.04	31	0.001	<20	0.27	0.023	0.07	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1	<0.2
1243913 Rock	0.046	20	69	0.85	38	0.241	<20	2.28	0.033	1.49	0.2	<0.01	0.8	2.53	8.6	<0.5	10	<0.2
REP 1243913 QC																		
REP 1247957 QC	0.012	6	17	0.36	69	0.052	<20	0.60	0.009	0.08	0.1	<0.01	<0.1	0.26	0.9	<0.5	2	<0.2
Core Reject Duplicates																		
1237459 Rock	0.009	13	20	0.35	127	0.033	<20	0.84	0.034	0.19	0.1	<0.01	<0.1	<0.05	1.6	<0.5	3	<0.2
DUP 1237459 QC	0.009	12	20	0.35	123	0.031	<20	0.80	0.026	0.17	0.1	<0.01	<0.1	<0.05	1.6	<0.5	3	<0.2
1247957 Rock	0.012	5	15	0.36	73	0.048	<20	0.58	0.007	0.08	0.2	<0.01	<0.1	0.26	1.0	<0.5	2	<0.2
DUP 1247957 QC	0.012	5	15	0.35	65	0.051	<20	0.58	0.008	0.08	0.2	<0.01	<0.1	0.25	0.9	<0.5	2	<0.2
Reference Materials																		
STD DS9 Standard	0.085	12	121	0.64	338	0.107	<20	0.96	0.080	0.40	2.7	0.20	5.5	0.17	2.1	5.9	5	5.6
STD DS9 Standard	0.086	14	122	0.65	352	0.114	<20	0.97	0.084	0.40	3.2	0.21	5.7	0.16	2.4	4.8	5	5.2
STD OREAS45EA Standard	0.029	8	879	0.10	152	0.095	<20	3.33	0.016	0.05	<0.1	0.01	<0.1	<0.05	76.5	0.9	13	<0.2
STD OREAS45EA Standard	0.031	7	882	0.10	147	0.096	<20	3.31	0.016	0.05	<0.1	0.01	<0.1	<0.05	82.3	<0.5	12	<0.2
STD OXK94 Standard																		
STD OXK94 Standard																		
STD SH55 Standard																		
STD SH55 Standard																		
STD SH55 Expected																		
STD OXK94 Expected																		
STD DS9 Expected	0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59	5.02
STD OREAS45EA Expected	0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7	0.11
BLK Blank																		
BLK Blank																		
BLK Blank																		
BLK Blank																		
BLK Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2

QUALITY CONTROL REPORT

WHI13000066.1

		WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	0.02	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1-WHI	Prep Blank		6	0.2	3.3	3.1	46	<0.1	2.6	4.0	555	1.93	<0.5	4.8	4.8	59	<0.1	<0.1	<0.1	35	0.54
G1-WHI	Prep Blank		<2	<0.1	3.0	3.2	48	<0.1	3.0	4.1	574	2.03	<0.5	<0.5	5.4	62	<0.1	<0.1	0.2	36	0.48

QUALITY CONTROL REPORT

WHI13000066.1

		1DX P %	1DX La ppm	1DX Cr ppm	1DX Mg %	1DX Ba ppm	1DX Ti %	1DX B ppm	1DX Al %	1DX Na %	1DX K %	1DX W ppm	1DX Hg ppm	1DX Tl ppm	1DX S %	1DX Sc ppm	1DX Se ppm	1DX Ga ppm	1DX Te ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.073	12	5	0.56	177	0.120	<20	0.97	0.083	0.50	<0.1	<0.01	0.3	<0.05	2.0	<0.5	4	<0.2
G1-WHI	Prep Blank	0.074	12	4	0.52	170	0.126	<20	0.98	0.094	0.50	<0.1	<0.01	0.4	<0.05	2.1	<0.5	5	<0.2