

Acme Analytical Laboratories (Vancouver) Ltd.
9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA
PHONE (604) 253-3158

Client: **Goldstrike Resources Ltd.**
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Submitted By: Email Distribution List
Receiving Lab: Canada-Whitehorse
Received: August 02, 2013
Report Date: August 23, 2013
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI13000224.1

CLIENT JOB INFORMATION

Project: Plateau South
Shipment ID: PLAS_ROCK_2013_11
P.O. Number
Number of Samples: 39

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Goldstrike Resources Ltd.
1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3
CANADA

CC:

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	39	Crush, split and pulverize 250 g rock to 200 mesh			WHI
3B	39	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1DX	39	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.

CERTIFICATE OF ANALYSIS

WHI13000224.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1241368	Rock	1.27	2	<0.1	11.5	4.0	2	<0.1	6.0	3.0	51	0.57	4.8	1.9	7.4	2	<0.1	<0.1	<0.1	<2
1241369	Rock	1.18	46	0.2	16.5	7.4	11	<0.1	12.6	5.3	330	1.21	102.8	18.3	19.9	17	<0.1	0.1	<0.1	<2
1241370	Rock	0.93	1095	0.1	19.9	22.7	57	0.2	19.8	6.2	138	2.44	529.2	1404	6.0	5	<0.1	0.2	0.2	8
1241371	Rock	0.85	17	0.2	22.5	21.1	47	<0.1	32.9	8.5	737	2.50	30.3	4.9	5.7	73	0.1	<0.1	0.2	5
1241372	Rock	1.57	4	<0.1	6.0	5.3	6	<0.1	5.5	2.3	186	0.59	3.5	<0.5	1.6	20	<0.1	<0.1	<0.1	<2
1241373	Rock	1.58	4333	0.1	15.7	277.1	134	1.1	19.9	8.4	192	2.08	5959	3222	3.6	20	0.3	1.5	1.7	<2
1241374	Rock	0.75	6	<0.1	4.0	29.8	3	0.1	4.0	1.7	161	0.51	7.4	5.2	0.1	10	<0.1	<0.1	0.4	<2
1241375	Rock	0.58	13	0.1	0.8	6.5	3	<0.1	1.8	0.6	46	0.37	449.1	10.1	1.3	1	<0.1	0.2	<0.1	<2
1241376	Rock	1.03	51	<0.1	3.3	2.1	3	<0.1	3.3	1.2	68	0.52	479.0	16.7	1.0	4	<0.1	0.2	<0.1	<2
1241377	Rock	0.88	132	<0.1	2.4	0.4	2	<0.1	1.0	0.4	35	0.49	503.8	203.2	<0.1	<1	<0.1	0.3	<0.1	<2
1235872	Rock	0.66	4	0.4	25.9	30.4	57	<0.1	21.4	9.7	114	3.17	29.0	1.9	11.5	8	<0.1	0.1	0.5	7
1235873	Rock	1.02	<2	<0.1	4.6	23.1	19	<0.1	7.0	2.8	792	1.18	8.3	0.6	3.4	9	<0.1	0.2	<0.1	<2
1235874	Rock	0.80	<2	<0.1	11.8	2.1	31	<0.1	10.5	3.5	1473	1.75	7.0	<0.5	6.0	95	<0.1	<0.1	<0.1	2
1235875	Rock	0.50	<2	<0.1	4.3	1.8	366	<0.1	99.3	24.1	399	18.99	30.0	9.4	2.6	3	<0.1	0.1	<0.1	50
1242953	Rock	0.66	1494	0.2	10.0	23.9	14	0.2	10.5	3.7	114	1.56	3385	1346	5.8	6	<0.1	0.6	0.3	<2
1243983	Rock	0.90	22	<0.1	1.1	2.4	8	<0.1	3.7	1.6	171	1.29	25.2	73.8	7.0	3	<0.1	0.3	<0.1	<2
1243984	Rock	0.82	101	0.1	2.2	4.7	4	<0.1	5.0	2.4	249	1.20	960.2	93.7	9.8	22	<0.1	0.4	<0.1	<2
1243985	Rock	1.19	54	0.2	18.7	15.2	31	<0.1	11.0	3.9	266	2.52	580.8	252.4	8.6	4	<0.1	0.2	<0.1	5
1243986	Rock	1.25	1460	0.2	4.0	40.1	9	0.1	8.5	3.8	284	1.84	7597	1829	6.1	11	0.2	2.4	0.6	<2
1243987	Rock	1.06	1479	<0.1	2.1	19.9	3	<0.1	4.6	2.7	292	1.28	6092	1551	3.4	6	<0.1	2.3	0.3	<2
1243988	Rock	0.98	747	0.2	2.8	31.2	8	<0.1	6.4	2.6	228	1.74	8407	723.0	4.3	16	<0.1	3.2	0.7	<2
1243989	Rock	1.47	130	0.3	3.7	5.2	34	<0.1	14.0	6.5	492	1.68	2719	205.9	8.1	55	<0.1	1.4	0.1	<2
1243990	Rock	0.85	209	0.3	5.0	6.6	15	<0.1	13.7	7.7	292	1.47	2014	182.8	5.0	6	0.2	0.7	0.1	<2
1243991	Rock	0.92	49	<0.1	2.6	3.8	3	<0.1	11.5	5.4	84	0.91	2014	80.2	5.0	4	<0.1	0.8	<0.1	<2
1243992	Rock	0.79	4806	0.2	8.4	10.5	7	0.5	4.0	2.5	50	1.75	7660	3862	8.5	6	<0.1	1.9	0.2	2
1243993	Rock	0.86	7273	0.3	18.6	15.2	3	0.8	17.8	10.4	36	3.21	>10000	8360	9.5	10	<0.1	4.8	1.3	<2
1243994	Rock	0.93	2188	0.3	4.3	2520	143	7.3	1.0	0.4	23	1.00	1894	3325	4.2	6	0.8	2.4	8.8	<2
1201901	Rock	0.38	17	0.1	1.3	8.3	3	0.1	1.8	0.7	144	0.49	112.7	21.0	1.2	2	<0.1	<0.1	0.2	<2
1201902	Rock	0.87	10	0.1	2.7	24.2	13	<0.1	2.1	1.3	242	1.24	60.5	10.8	4.4	3	<0.1	0.3	0.1	<2
1201903	Rock	0.64	4	<0.1	4.5	8.6	22	<0.1	3.0	2.0	235	1.72	93.9	1.8	9.2	3	<0.1	<0.1	<0.1	2

CERTIFICATE OF ANALYSIS

WHI13000224.1

Method Analyte Unit MDL		1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
1241368	Rock	0.005	36	30	0.01	6	<0.001	<20	0.04	0.004	0.01	<0.1	<0.01	<0.1	0.16	0.2	<0.5	<1	<0.2
1241369	Rock	0.009	23	16	0.07	51	<0.001	<20	0.22	0.069	0.05	<0.1	<0.01	<0.1	0.14	1.0	<0.5	<1	<0.2
1241370	Rock	0.013	7	17	0.48	71	0.002	<20	0.87	0.029	0.06	<0.1	<0.01	<0.1	0.25	1.5	<0.5	3	1.0
1241371	Rock	0.010	6	22	0.59	17	<0.001	<20	0.63	0.035	0.04	<0.1	<0.01	<0.1	0.20	2.9	0.7	2	<0.2
1241372	Rock	0.019	2	26	0.08	6	<0.001	<20	0.07	0.011	0.02	<0.1	<0.01	<0.1	0.08	0.2	<0.5	<1	<0.2
1241373	Rock	0.005	4	28	0.12	8	<0.001	<20	0.16	0.021	0.02	<0.1	<0.01	<0.1	0.98	0.8	0.5	<1	0.4
1241374	Rock	0.004	<1	29	0.06	1	<0.001	<20	0.01	0.002	<0.01	<0.1	<0.01	0.2	<0.05	0.2	<0.5	<1	<0.2
1241375	Rock	0.003	2	25	0.01	6	<0.001	<20	0.04	0.016	<0.01	<0.1	<0.01	<0.1	<0.05	0.2	<0.5	<1	<0.2
1241376	Rock	0.020	1	32	0.02	9	<0.001	<20	0.05	0.007	0.01	<0.1	<0.01	<0.1	<0.05	0.3	<0.5	<1	<0.2
1241377	Rock	<0.001	<1	27	<0.01	35	<0.001	<20	<0.01	0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
1235872	Rock	0.016	18	19	0.49	188	0.001	<20	1.29	0.012	0.24	<0.1	<0.01	<0.1	0.07	1.1	<0.5	4	<0.2
1235873	Rock	0.014	6	20	0.05	30	<0.001	<20	0.22	0.021	0.05	<0.1	<0.01	<0.1	0.08	0.6	<0.5	<1	<0.2
1235874	Rock	0.007	9	15	0.17	14	<0.001	<20	0.36	0.029	0.08	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1	<0.2
1235875	Rock	0.003	2	18	3.64	23	0.008	<20	8.86	0.003	0.04	<0.1	0.01	<0.1	<0.05	2.8	<0.5	25	<0.2
1242953	Rock	0.011	10	16	0.05	66	<0.001	<20	0.22	0.024	0.06	<0.1	0.01	<0.1	0.30	0.6	<0.5	<1	<0.2
1243983	Rock	0.015	9	14	0.06	20	<0.001	<20	0.22	0.038	0.03	<0.1	<0.01	<0.1	0.15	1.2	<0.5	<1	<0.2
1243984	Rock	0.021	10	19	0.10	425	<0.001	<20	0.11	0.052	0.06	<0.1	<0.01	<0.1	0.32	1.0	<0.5	<1	<0.2
1243985	Rock	0.006	8	25	0.32	47	0.001	<20	0.58	0.024	0.05	<0.1	<0.01	<0.1	0.25	1.5	<0.5	1	<0.2
1243986	Rock	0.011	9	15	0.02	238	<0.001	<20	0.19	0.037	0.05	<0.1	0.01	<0.1	0.41	1.0	1.0	<1	0.9
1243987	Rock	0.007	6	20	<0.01	96	<0.001	<20	0.10	0.027	0.03	<0.1	0.02	<0.1	0.28	0.7	<0.5	<1	0.5
1243988	Rock	0.009	6	16	0.01	241	<0.001	<20	0.11	0.036	0.04	<0.1	0.01	<0.1	0.52	0.6	<0.5	<1	1.8
1243989	Rock	0.006	12	23	0.22	25	<0.001	<20	0.17	0.048	0.05	<0.1	<0.01	<0.1	0.13	1.7	<0.5	<1	<0.2
1243990	Rock	0.009	6	21	0.03	119	<0.001	<20	0.17	0.031	0.03	<0.1	<0.01	<0.1	0.27	1.1	<0.5	<1	0.3
1243991	Rock	0.002	7	21	<0.01	12	<0.001	<20	0.10	0.051	0.03	<0.1	<0.01	<0.1	0.14	0.4	<0.5	<1	0.3
1243992	Rock	0.007	11	18	0.04	28	<0.001	<20	0.19	0.029	0.08	0.1	<0.01	<0.1	0.38	0.8	<0.5	<1	0.8
1243993	Rock	0.011	10	12	0.02	63	<0.001	<20	0.19	0.026	0.09	0.3	0.02	<0.1	0.72	0.6	0.9	<1	0.8
1243994	Rock	0.007	8	20	<0.01	6	<0.001	<20	0.11	0.041	0.02	<0.1	0.05	<0.1	0.25	0.3	1.7	<1	<0.2
1201901	Rock	0.004	2	23	<0.01	5	<0.001	<20	0.05	0.017	0.01	<0.1	<0.01	<0.1	<0.05	0.2	<0.5	<1	<0.2
1201902	Rock	0.010	7	22	0.10	12	<0.001	<20	0.26	0.022	0.02	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	<1	<0.2
1201903	Rock	0.010	14	18	0.19	11	<0.001	<20	0.46	0.034	0.04	<0.1	<0.01	<0.1	<0.05	1.0	<0.5	1	<0.2

CERTIFICATE OF ANALYSIS

WHI13000224.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1201904	Rock	0.59	2	<0.1	18.9	9.9	7	<0.1	8.4	2.7	132	0.67	10.6	1.2	2.9	3	<0.1	<0.1	<0.1	<2
1201905	Rock	1.19	47	<0.1	4.4	15.7	11	<0.1	5.4	2.1	164	1.11	75.2	11.3	6.5	4	<0.1	<0.1	<0.1	<2
1201906	Rock	0.72	17	0.1	7.3	10.9	56	<0.1	27.4	12.0	373	1.24	223.7	6.4	3.5	7	0.3	0.2	<0.1	<2
1201907	Rock	1.15	7	0.1	5.3	2.5	10	<0.1	7.5	2.8	329	1.11	23.0	7.8	4.9	6	<0.1	<0.1	<0.1	5
1237496	Rock	1.33	2	0.1	11.8	7.2	45	<0.1	17.4	5.1	319	2.86	4.0	1.2	5.1	4	<0.1	<0.1	<0.1	7
1237497	Rock	0.78	47	<0.1	5.3	11.0	16	<0.1	7.2	2.7	151	1.04	176.6	36.3	3.8	3	<0.1	<0.1	<0.1	4
1237498	Rock	0.47	2	<0.1	2.3	8.4	11	<0.1	9.3	1.9	180	0.72	2.0	<0.5	1.3	1	<0.1	<0.1	<0.1	<2
1237499	Rock	0.85	63	<0.1	14.9	7.3	15	<0.1	6.0	2.0	140	1.53	90.2	37.3	8.6	4	<0.1	0.1	<0.1	3
1237500	Rock	0.79	8	0.1	2.8	3.6	9	<0.1	3.6	1.4	384	0.76	286.2	7.4	7.7	23	<0.1	0.2	<0.1	<2

Acme Analytical Laboratories (Vancouver) Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.

1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Project: Plateau South

Report Date: August 23, 2013

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI13000224.1

	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga
	Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm
	MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1
1201904	Rock	0.005	12	27	0.03	2	<0.001	<20	0.07	0.008	<0.01	<0.1	0.01	<0.1	<0.05	0.3	<0.5	<1
1201905	Rock	0.010	9	22	0.11	10	<0.001	<20	0.27	0.057	0.02	<0.1	<0.01	<0.1	0.12	1.0	<0.5	<1
1201906	Rock	0.004	6	21	0.07	36	<0.001	<20	0.21	0.033	0.01	<0.1	<0.01	<0.1	0.15	1.1	<0.5	<1
1201907	Rock	0.010	7	20	0.10	19	<0.001	29	0.30	0.030	0.06	<0.1	<0.01	<0.1	0.16	0.8	<0.5	1
1237496	Rock	0.014	7	22	0.56	9	0.003	27	1.20	0.007	0.04	<0.1	<0.01	<0.1	<0.05	1.1	<0.5	4
1237497	Rock	0.009	6	20	0.11	16	<0.001	30	0.32	0.029	0.04	<0.1	<0.01	<0.1	0.08	1.1	<0.5	<1
1237498	Rock	0.003	3	24	0.03	7	<0.001	39	0.13	0.010	0.03	<0.1	<0.01	<0.1	<0.05	0.4	<0.5	<1
1237499	Rock	0.008	9	20	0.10	53	<0.001	<20	0.29	0.017	0.06	<0.1	<0.01	<0.1	0.13	1.0	<0.5	<1
1237500	Rock	0.002	10	16	0.08	24	<0.001	<20	0.08	0.032	0.02	<0.1	<0.01	<0.1	<0.05	0.9	<0.5	<1

QUALITY CONTROL REPORT

WHI13000224.1

	Method	WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
Pulp Duplicates																					
1241372	Rock	1.57	4	<0.1	6.0	5.3	6	<0.1	5.5	2.3	186	0.59	3.5	<0.5	1.6	20	<0.1	<0.1	<0.1	<2	0.42
REP 1241372	QC		3																		
REP 1243988	QC		813																		
REP 1243988	QC			0.1	2.5	33.1	8	<0.1	7.9	2.9	249	1.78	8439	830.4	5.2	18	0.1	3.3	0.9	<2	0.05
Core Reject Duplicates																					
1243988	Rock	0.98	747	0.2	2.8	31.2	8	<0.1	6.4	2.6	228	1.74	8407	723.0	4.3	16	<0.1	3.2	0.7	<2	0.05
DUP 1243988	QC		639	0.1	2.4	30.2	8	<0.1	7.7	3.0	243	1.74	8192	632.0	4.3	16	0.1	3.0	0.7	<2	0.05
Reference Materials																					
STD DS9	Standard			12.9	108.2	120.6	320	1.7	40.5	7.7	609	2.41	26.6	107.0	6.1	73	2.5	3.2	6.3	40	0.71
STD DS9	Standard			12.2	115.6	139.1	320	1.7	42.8	7.5	599	2.41	26.5	124.0	6.7	70	2.4	4.0	6.8	41	0.70
STD OREAS45EA	Standard			1.2	683.4	13.7	32	0.2	367.2	52.8	406	23.93	7.4	53.1	10.2	4	<0.1	0.1	0.3	293	0.04
STD OREAS45EA	Standard			1.2	681.2	15.3	29	0.2	360.2	53.2	407	24.30	6.5	45.0	10.8	3	<0.1	0.1	0.3	276	0.04
STD OXC109	Standard		197																		
STD OXC109	Standard		202																		
STD OXC109	Standard		204																		
STD OXC109	Standard		205																		
STD OXI96	Standard		1785																		
STD OXI96	Standard		1881																		
STD OXI96	Standard		1864																		
STD OXI96	Standard		1858																		
STD OXC109 Expected			201																		
STD OXI96 Expected			1802																		
STD DS9 Expected				12.84	108	126	317	1.83	40.3	7.6	575	2.33	25.5	118	6.38	69.6	2.4	4.94	6.32	40	0.7201
STD OREAS45EA Expected				1.78	709	14.3	30.6	0.311	357	52	400	22.65	11.4	53	10.7	4.05	0.03	0.64	0.26	295	0.032
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		3																		

QUALITY CONTROL REPORT

WHI13000224.1

		Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
		Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Tl	S	Sc	Se	Ga
		Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	%	ppm	ppm	ppm
		MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1
Pulp Duplicates																			
1241372	Rock		0.019	2	26	0.08	6	<0.001	<20	0.07	0.011	0.02	<0.1	<0.01	<0.1	0.08	0.2	<0.5	<1
REP 1241372	QC																		
REP 1243988	QC																		
REP 1243988	QC		0.010	6	17	0.01	263	<0.001	<20	0.11	0.034	0.04	<0.1	0.01	<0.1	0.51	0.6	0.6	<1
Core Reject Duplicates																			
1243988	Rock		0.009	6	16	0.01	241	<0.001	<20	0.11	0.036	0.04	<0.1	0.01	<0.1	0.52	0.6	<0.5	<1
DUP 1243988	QC		0.009	6	15	0.01	246	<0.001	<20	0.10	0.033	0.04	<0.1	0.02	<0.1	0.51	0.7	<0.5	<1
Reference Materials																			
STD DS9	Standard		0.081	12	122	0.63	322	0.109	<20	0.95	0.083	0.40	2.7	0.19	5.3	0.17	2.3	4.5	4
STD DS9	Standard		0.084	12	121	0.63	319	0.104	<20	0.93	0.080	0.41	2.8	0.20	5.2	0.18	2.1	5.4	4
STD OREAS45EA	Standard		0.027	7	846	0.10	143	0.092	<20	3.10	0.019	0.05	<0.1	0.01	<0.1	<0.05	76.8	<0.5	13
STD OREAS45EA	Standard		0.027	7	844	0.09	143	0.086	<20	3.03	0.025	0.05	<0.1	0.02	<0.1	<0.05	71.3	0.6	12
STD OXC109	Standard																		
STD OXC109	Standard																		
STD OXC109	Standard																		
STD OXC109	Standard																		
STD OXI96	Standard																		
STD OXI96	Standard																		
STD OXI96	Standard																		
STD OXI96	Standard																		
STD OXC109 Expected																			
STD OXI96 Expected																			
STD DS9 Expected			0.0819	13.3	121	0.6165	330	0.1108		0.9577	0.0853	0.395	2.89	0.2	5.3	0.1615	2.5	5.2	4.59
STD OREAS45EA Expected			0.029	8.19	849	0.095	148	0.106		3.32	0.027	0.053		0.34	0.072	0.044	78	2.09	11.7
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		

QUALITY CONTROL REPORT

WHI13000224.1

		WGHT	3B	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	2	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	2.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	1.0	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
G1-WHI	Prep Blank		<2	0.1	1.7	3.7	45	<0.1	2.4	4.3	573	1.91	0.9	2.7	6.9	61	<0.1	<0.1	<0.1	38	0.53
G1-WHI	Prep Blank		<2	<0.1	2.9	3.9	42	<0.1	2.7	4.3	576	2.01	0.7	2.5	6.7	65	<0.1	<0.1	<0.1	38	0.52

Acme Analytical Laboratories (Vancouver) Ltd.

9050 Shaughnessy St Vancouver BC V6P 6E5 CANADA

PHONE (604) 253-3158

Client: Goldstrike Resources Ltd.

1300 - 1111 West Georgia Street
Vancouver BC V6E 4M3 CANADA

Project: Plateau South

Report Date: August 23, 2013

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI13000224.1

		1DX P %	1DX La ppm	1DX Cr ppm	1DX Mg %	1DX Ba ppm	1DX Ti %	1DX B ppm	1DX Al %	1DX Na %	1DX K %	1DX W ppm	1DX Hg ppm	1DX Tl ppm	1DX S %	1DX Sc ppm	1DX Se ppm	1DX Ga ppm	1DX Te ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.05	0.1	0.5	1	0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.05	<0.1	<0.5	<1	<0.2
Prep Wash																			
G1-WHI	Prep Blank	0.077	13	11	0.51	170	0.128	<20	0.99	0.109	0.52	<0.1	<0.01	0.3	<0.05	2.6	0.6	5	<0.2
G1-WHI	Prep Blank	0.072	13	12	0.49	167	0.135	<20	1.02	0.124	0.53	<0.1	<0.01	0.3	<0.05	2.5	<0.5	5	<0.2