

Sample #	Zone	Location	Interval Width (m)	Original Assay		Cyanidation		Cyanide Recovery	
				Au	Ag	Au	Ag	%Au	%Ag
N815163	Dickson	TR-12-01	1.97	5.01	49	4.24	44.17	85%	90%
N815150	Dickson	TR-12-01	4.45	1.435	11.9	1.41	9.5	98%	80%
N897615	Dickson	TR-12-02	1.6	10.85	93.6	8.57	60.19	79%	64%
N895052	Dickson	TR-12-02	2.32	1.2	44.4	0.9	23.44	75%	53%
N897570	Dickson	TR-12-02	0.8	1.005	19.3	1.1	11.6	109%	60%
N897632	Dickson	TR-12-02	1.82	1.765	1.28	1.82	1.23	103%	96%
N897651	Dickson	TR-12-02	0.8	1.38	6.49	1.18	2.86	86%	44%
N829923	Eastern Klaza	TR-12-08	0.63	2.15	50.3	2.03	14.43	94%	29%
N829949	Eastern Klaza	TR-12-08	0.58	8.89	10.75	7.29	9.52	82%	89%
N829950	Eastern Klaza	TR-12-08	0.82	1.695	4.62	1.5	2.49	88%	54%
N829952	Eastern Klaza	TR-12-08	0.64	4.25	2.97	2.63	1.66	62%	56%
N829954	Eastern Klaza	TR-12-08	1.7	1.675	1.17	1.71	0.7	102%	60%
N829957	Eastern Klaza	TR-12-08	0.95	1.755	3.61	1.44	1.88	82%	52%
N828609	Eastern Klaza	TR-12-08	1.25	1.405	16.75	1.06	5.83	75%	35%
N828613	Eastern Klaza	TR-12-08	0.61	1.665	56.2	1.53	22.56	92%	40%
N828664	Eastern Klaza	TR-12-08	0.88	1.21	50.9	1.14	16.67	94%	33%
N828743	Eastern Klaza	TR-12-08	1.46	1.285	53.4	0.88	39.36	68%	74%
N815550	BRX	TR-12-23	0.9	5.46	82.6	4.67	57.14	86%	69%
N815548	BRX	TR-12-23	1.1	1.785	49	2.47	13.1	138%	27%
N815549	BRX	TR-12-23	1.4	2.6	95.4	1.49	23.65	57%	25%
M897808	Western Klaza	TR-12-35	1.25	3.32	66.1	3.25	56.56	98%	86%
M897807	Western Klaza	TR-12-35	1	8.29	452	7.12	308.7	86%	68%
N815075	Dickson Ext.	TR-12-36	2.3	5.73	279	4.81	219.9	84%	79%
N815076	Dickson Ext.	TR-12-36	2.5	6.7	355	6.15	260.5	92%	73%
N815077	Dickson Ext.	TR-12-36	2	1.075	64.2	1.03	56.97	96%	89%
N815078	Dickson Ext.	TR-12-36	2.4	1.18	39.5	1.01	37.04	86%	94%
N815760	Porphyry/ BRX	TR-12-39	1.05	1.115	34.4	1.1	16.03	99%	47%
N815992	Porphyry/ BRX	TR-12-39	1.4	1.38	31.6	1.63	4.69	118%	15%
M355705	Porphyry/ BRX	TR-12-39	3	1.46	5.23	1.24	2.11	85%	40%
M355793	Porphyry/ BRX	TR-12-39	1.35	8.41	26.1	8.24	9.88	98%	38%
							<b>Avg</b>	<b>90%</b>	<b>59%</b>

Sample #	Zone	Location		Original Assay		Cyanidation		Cyanide Recovery	
				Au	Ag	Au	Ag	%Au	%Ag
N829003	BYG	KL-12-65	1.00	2.78	20	0.8	7.28	29%	36%
N829456	BYG	KL-12-66	1.00	1.05	6.06	0.82	3.57	78%	59%
M899397	Dickson	KL-12-81	1.87	0.788	22.2	0.58	8.11	74%	37%
N810298	Pika	KL-12-89	2.20	3.84	43.2	2.29	19.71	60%	46%
M355249	BRX	KL-12-103	1.00	1.155	35.7	0.62	16.95	54%	47%
M355256	BRX	KL-12-103	1.52	1.895	111	0.5	52.45	26%	47%
N811891	AEX	KL-12-109	1.99	1.285	24.7	1.06	3.65	82%	15%
N813344	AEX	KL-12-112	1.00	5.3	5.5	5.24	3.21	99%	58%
N814751	BRX	KL-12-114	1.17	2.13	1.82	0.78	1.14	37%	63%
N814750	BRX	KL-12-114	1.10	11.9	313	9.54	78.2	80%	25%
M357197	Western Klaza	KL-12-124	2.62	1.33	42.6	1.02	24.1	77%	57%
M357420	AEX	KL-12-125	1.53	2.53	0.47	1.63	0.35	64%	74%
M357427	AEX	KL-12-125	1.27	0.986	7.34	1.04	5.61	105%	76%
M357647	Western Klaza	KL-12-127	1.05	1.72	94.8	0.49	46.98	28%	50%
M359904	Dickson	KL-12-130	1.15	2.55	5.13	0.72	2.74	28%	53%
M356616	AEX	KL-12-132	1.66	2.31	1.55	0.47	1	20%	65%
M356624	AEX	KL-12-132	1.39	1.425	14.95	0.54	4.26	38%	28%
M356626	AEX	KL-12-132	1.16	4.66	2.91	1.25	1.4	27%	48%
M356641	AEX	KL-12-132	1.09	2.38	2.49	0.86	1.21	36%	49%
M356140	BYG	KL-12-133	2.62	1.3	37.4	0.8	19.01	62%	51%
M356139	BYG	KL-12-133	2.74	0.719	23.4	0.61	7.55	85%	32%
							<b>Avg</b>	<b>57%</b>	<b>48%</b>