



Certificate of Analysis
Work Order : VC162356
[Report File No.: 0000018486]

Date: August 16, 2016

To: Kendra Johnston
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA ST
VACOUVER BC V6B 4N8

P.O. No.: Boulevard - YK16-BLVD8
Project No.: IGO YUKON
Samples: 53
Received: Aug 2, 2016
Pages: Page 1 to 11
(Inclusive of Cover Sheet)

Methods Summary

| <u>No. Of Samples</u> | <u>Method Code</u> | <u>Description</u> |
|-----------------------|--------------------|--|
| 53 | G_LOG02 | Pre-preparation processing, sorting, logging, boxing |
| 53 | G_WGH79 | Weighing of samples and reporting of weights |
| 51 | G_PRP89 | Weigh, dry,(up to 3.0 kg) crush to 75% passing 2 mm, split 250 g, pulverize to |
| 53 | GE_FAA313 | @Au, FAS, AAS, 30g-5ml(Final Mode) |
| 53 | GE_IMS14 | Aqua Regia digestion |

Certified By : _____

John Chiang
QC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method

M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Methods marked with an asterisk (e.g. *NAA08V) were subcontracted

Elements marked with the @ symbol (e.g. @Cu) denote assays performed using accredited test methods

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

| Element Method Det.Lim. Units | WtKg G_WGH79 0.01 kg | @Au GE_FAA313 5 ppb | Ag GE_IMS14B 0.01 ppm | Al GE_IMS14B 0.01 % | As GE_IMS14B 1 ppm | Ba GE_IMS14B 5 ppm | Bi GE_IMS14B 0.02 ppm | Ca GE_IMS14B 0.01 % |
|--|-------------------------------|------------------------------|--------------------------------|------------------------------|-----------------------------|-----------------------------|--------------------------------|------------------------------|
| B00312896 | 2.830 | <5 | 0.10 | 0.40 | 5 | 94 | 0.23 | 1.36 |
| B00312897 | 2.135 | <5 | 0.24 | 0.58 | 12 | 87 | 0.53 | 1.07 |
| B00312898 | 2.760 | 6 | 0.07 | 0.59 | 5 | 72 | 0.12 | 0.89 |
| B00312899 | 2.585 | <5 | 0.04 | 0.94 | 4 | 80 | 0.10 | 0.82 |
| B00312900 | 3.115 | <5 | 0.03 | 1.73 | 2 | 180 | 0.02 | 1.38 |
| B00312901 | 3.025 | <5 | 0.07 | 1.46 | 1 | 173 | 0.09 | 1.33 |
| B00312902 | 2.995 | <5 | 0.05 | 1.16 | <1 | 120 | 0.09 | 1.66 |
| B00312903 | 2.575 | <5 | 0.09 | 2.38 | <1 | 113 | 0.14 | 2.14 |
| B00312904 | 3.130 | <5 | 0.05 | 2.11 | 1 | 120 | 0.09 | 1.46 |
| B00312905 | 2.830 | <5 | 0.04 | 0.62 | <1 | 34 | 0.18 | 0.59 |
| B00312906 | 2.885 | <5 | 0.05 | 1.14 | <1 | 61 | 0.11 | 0.93 |
| B00312907 | 2.790 | <5 | 0.07 | 0.46 | <1 | 47 | 0.23 | 0.83 |
| B00312908 | 3.305 | <5 | 0.04 | 1.44 | 1 | 114 | 0.09 | 1.65 |
| B00312909 | 3.560 | <5 | 0.05 | 1.49 | 1 | 117 | 0.07 | 1.42 |
| B00312910 | 2.265 | <5 | 0.04 | 1.37 | <1 | 96 | 0.09 | 1.19 |
| B00312911 | 2.660 | <5 | 0.04 | 1.31 | 1 | 104 | 0.09 | 1.38 |
| B00312912 | 3.305 | <5 | 0.03 | 0.72 | 1 | 40 | 0.14 | 0.85 |
| B00312913 | 2.640 | <5 | 0.05 | 1.08 | 5 | 102 | 0.13 | 1.13 |
| B00312914 | 2.895 | <5 | 0.07 | 1.33 | 6 | 119 | 0.16 | 1.15 |
| B00312915 | 2.895 | <5 | 0.05 | 1.92 | 1 | 125 | 0.12 | 1.38 |
| B00312916 | 2.675 | <5 | 0.04 | 2.36 | 1 | 244 | 0.20 | 1.17 |
| B00312917 | 2.395 | <5 | 0.03 | 0.77 | 1 | 87 | 0.11 | 0.22 |
| B00312918 | 2.450 | <5 | 0.03 | 1.04 | <1 | 187 | 0.41 | 0.34 |
| B00312919 | 2.730 | <5 | 0.05 | 0.53 | 2 | 88 | 0.41 | 0.18 |
| B00312920 | 0.115 | <5 | 0.06 | 1.61 | <1 | 112 | 0.07 | 0.94 |
| B00312921 | 2.310 | <5 | 0.05 | 0.26 | <1 | 39 | 0.37 | 0.19 |
| B00312922 | 2.760 | <5 | 0.04 | 0.26 | <1 | 31 | 0.34 | 0.27 |
| B00312923 | 2.655 | <5 | 0.04 | 0.19 | <1 | 15 | 0.37 | 0.29 |
| B00312924 | 2.510 | <5 | 0.03 | 0.28 | 1 | 15 | 0.25 | 0.20 |
| B00312925 | 2.550 | <5 | 0.06 | 0.13 | <1 | 29 | 0.07 | 0.50 |
| B00312926 | 2.935 | <5 | 0.03 | 0.23 | 1 | 27 | 0.17 | 0.57 |
| B00312927 | 2.765 | <5 | 0.05 | 0.60 | 11 | 220 | 0.19 | 0.48 |
| B00312928 | 2.770 | <5 | 0.11 | 0.60 | 2 | 430 | 0.32 | 0.29 |
| B00312929 | 2.540 | <5 | 0.09 | 0.37 | 1 | 110 | 0.85 | 0.27 |
| *Dup B00312929 | N.A. | <5 | 0.09 | 0.39 | 1 | 114 | 0.95 | 0.28 |
| B00312930 | 0.115 | 5310 | 0.81 | 2.30 | 34 | 170 | 0.31 | 1.34 |
| B00312931 | 2.460 | <5 | 0.07 | 0.69 | 4 | 68 | 0.67 | 0.32 |
| B00312932 | 2.295 | <5 | 0.11 | 0.17 | 9 | 20 | 0.89 | 0.12 |
| B00312933 | 2.875 | 17 | 0.06 | 0.25 | 2270 | 265 | 0.42 | 1.15 |
| B00312934 | 2.875 | <5 | 0.08 | 0.30 | 83 | 50 | 0.70 | 0.51 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | WtKg G_WGH79 0.01 kg | @Au GE_FAA313 5 ppb | Ag GE_IMS14B 0.01 ppm | Al GE_IMS14B 0.01 % | As GE_IMS14B 1 ppm | Ba GE_IMS14B 5 ppm | Bi GE_IMS14B 0.02 ppm | Ca GE_IMS14B 0.01 % |
|--|-------------------------------|------------------------------|--------------------------------|------------------------------|-----------------------------|-----------------------------|--------------------------------|------------------------------|
| B00312935 | 2.725 | <5 | 0.09 | 0.40 | 13 | 54 | 0.82 | 0.41 |
| B00312936 | 2.990 | <5 | 0.07 | 0.34 | 9 | 55 | 0.78 | 0.42 |
| B00312937 | 2.800 | <5 | 0.05 | 0.30 | 3 | 66 | 0.77 | 0.33 |
| B00312938 | 2.870 | <5 | 0.03 | 0.22 | 4 | 36 | 0.06 | 0.14 |
| B00312939 | 3.035 | <5 | 0.06 | 0.17 | 6 | 24 | 0.20 | 0.38 |
| B00312940 | 2.190 | 179 | 0.24 | 1.44 | 327 | 323 | 6.41 | 0.83 |
| B00312941 | 2.405 | 177 | 0.23 | 1.42 | 297 | 308 | 6.90 | 0.81 |
| B00312942 | 2.950 | <5 | 0.20 | 1.51 | 90 | 377 | 0.32 | 0.63 |
| B00312943 | 2.750 | <5 | 0.22 | 1.18 | 12 | 392 | 0.14 | 0.56 |
| B00312944 | 2.950 | 15 | 0.23 | 1.21 | 92 | 439 | 0.29 | 0.37 |
| B00312945 | 2.745 | 7 | 0.21 | 1.26 | 13 | 456 | 0.19 | 0.34 |
| B00312946 | 2.660 | 7 | 0.16 | 1.41 | 31 | 447 | 0.37 | 0.42 |
| B00312947 | 2.695 | 27 | 0.39 | 1.25 | 720 | 398 | 14.7 | 0.48 |
| B00312948 | 2.480 | 14 | 0.24 | 1.21 | 46 | 467 | 5.82 | 0.36 |
| *Rep B00312897 | | <5 | | | | | | |
| *Rep B00312938 | | <5 | | | | | | |
| *Std OREAS151B | | 67 | | | | | | |
| *Std OXB130 | | 126 | | | | | | |
| *Std OXH97 | | 1320 | | | | | | |
| *Blk BLANK | | <5 | | | | | | |
| *Rep B00312919 | | | 0.05 | 0.54 | 2 | 85 | 0.40 | 0.19 |
| *Rep B00312946 | | | 0.18 | 1.39 | 37 | 479 | 0.40 | 0.43 |
| *Std OREAS922 | | | 0.77 | 2.72 | 5 | 69 | 10.3 | 0.35 |
| *Std OREAS209 | | | 0.25 | 1.25 | 1010 | 78 | 0.06 | 1.55 |
| *Blk BLANK | | | <0.01 | <0.01 | <1 | <5 | <0.02 | <0.01 |
| *Blk BLANK | | | <0.01 | <0.01 | <1 | <5 | <0.02 | <0.01 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | Cd GE_IMS14B 0.01 ppm | Ce GE_IMS14B 0.05 ppm | Co GE_IMS14B 0.1 ppm | Cr GE_IMS14B 1 ppm | Cu GE_IMS14B 0.5 ppm | Fe GE_IMS14B 0.01 % | Ga GE_IMS14B 0.1 ppm | Hg GE_IMS14B 0.01 ppm |
|--|--------------------------------|--------------------------------|-------------------------------|-----------------------------|-------------------------------|------------------------------|-------------------------------|--------------------------------|
| B00312896 | 0.50 | 61.6 | 5.2 | 12 | 19.6 | 2.74 | 3.0 | <0.01 |
| B00312897 | 0.38 | 84.5 | 5.5 | 10 | 32.6 | 3.55 | 4.5 | <0.01 |
| B00312898 | 0.16 | 69.4 | 4.0 | 9 | 12.1 | 2.46 | 5.3 | <0.01 |
| B00312899 | 0.11 | 70.1 | 7.2 | 13 | 13.4 | 2.89 | 8.6 | <0.01 |
| B00312900 | 0.08 | 27.7 | 15.4 | 55 | 29.5 | 3.24 | 8.1 | <0.01 |
| B00312901 | 0.17 | 51.9 | 10.6 | 26 | 23.9 | 3.70 | 11.3 | <0.01 |
| B00312902 | 0.17 | 47.0 | 9.5 | 28 | 19.6 | 3.25 | 8.2 | <0.01 |
| B00312903 | 0.19 | 6.11 | 22.1 | 162 | 35.0 | 3.45 | 9.4 | <0.01 |
| B00312904 | 0.10 | 18.5 | 19.8 | 132 | 28.0 | 2.87 | 6.4 | <0.01 |
| B00312905 | 0.11 | 74.9 | 4.3 | 17 | 7.4 | 2.55 | 5.4 | <0.01 |
| B00312906 | 0.14 | 128 | 10.3 | 55 | 16.9 | 3.00 | 7.3 | <0.01 |
| B00312907 | 0.22 | 118 | 2.8 | 13 | 17.4 | 2.47 | 5.0 | <0.01 |
| B00312908 | 0.10 | 49.4 | 14.0 | 73 | 21.3 | 3.06 | 7.5 | <0.01 |
| B00312909 | 0.11 | 65.0 | 12.6 | 36 | 20.9 | 3.70 | 10.8 | <0.01 |
| B00312910 | 0.08 | 72.5 | 11.2 | 42 | 21.2 | 3.23 | 10.3 | <0.01 |
| B00312911 | 0.10 | 72.1 | 11.9 | 42 | 17.4 | 3.43 | 10.2 | <0.01 |
| B00312912 | 0.18 | 87.2 | 5.1 | 26 | 12.2 | 2.64 | 6.3 | <0.01 |
| B00312913 | 0.33 | 72.1 | 7.0 | 33 | 18.4 | 3.03 | 7.2 | <0.01 |
| B00312914 | 0.26 | 43.6 | 8.7 | 40 | 21.8 | 2.76 | 5.5 | <0.01 |
| B00312915 | 0.23 | 34.3 | 4.5 | 11 | 8.8 | 2.79 | 6.8 | <0.01 |
| B00312916 | 0.06 | 72.1 | 11.7 | 40 | 24.9 | 3.34 | 8.5 | <0.01 |
| B00312917 | 0.08 | 62.3 | 5.2 | 23 | 13.8 | 2.38 | 4.3 | <0.01 |
| B00312918 | 0.08 | 50.3 | 8.1 | 36 | 29.4 | 2.64 | 6.7 | <0.01 |
| B00312919 | 0.08 | 51.3 | 4.4 | 19 | 30.4 | 1.88 | 2.8 | <0.01 |
| B00312920 | 0.05 | 14.8 | 8.9 | 11 | 66.2 | 2.90 | 4.9 | <0.01 |
| B00312921 | 0.15 | 76.0 | 1.4 | 14 | 16.6 | 1.68 | 3.1 | <0.01 |
| B00312922 | 0.21 | 108 | 1.0 | 13 | 15.3 | 1.66 | 3.5 | <0.01 |
| B00312923 | 0.11 | 119 | 1.2 | 10 | 8.2 | 1.55 | 2.5 | <0.01 |
| B00312924 | 0.16 | 82.3 | 1.0 | 13 | 12.9 | 1.47 | 3.4 | <0.01 |
| B00312925 | 0.06 | 66.9 | 1.9 | 15 | 12.8 | 1.55 | 1.5 | <0.01 |
| B00312926 | 0.07 | 118 | 1.2 | 13 | 11.1 | 1.47 | 2.8 | <0.01 |
| B00312927 | 0.26 | 65.1 | 3.9 | 30 | 21.7 | 1.90 | 4.4 | <0.01 |
| B00312928 | 0.30 | 30.0 | 4.5 | 37 | 23.0 | 1.74 | 3.6 | <0.01 |
| B00312929 | 0.21 | 41.1 | 1.8 | 19 | 29.2 | 1.16 | 2.9 | <0.01 |
| *Dup B00312929 | 0.21 | 39.2 | 1.8 | 20 | 32.4 | 1.22 | 2.8 | <0.01 |
| B00312930 | 0.16 | 16.4 | 16.2 | 89 | 106 | 4.20 | 6.4 | 0.11 |
| B00312931 | 0.12 | 46.9 | 4.1 | 59 | 29.1 | 1.71 | 3.6 | <0.01 |
| B00312932 | 0.29 | 30.8 | 1.0 | 13 | 26.5 | 1.05 | 1.3 | <0.01 |
| B00312933 | 0.38 | 21.2 | 2.6 | 12 | 16.3 | 1.74 | 1.1 | <0.01 |
| B00312934 | 0.24 | 40.0 | 2.2 | 24 | 12.7 | 1.60 | 2.3 | <0.01 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | Cd GE_IMS14B 0.01 ppm | Ce GE_IMS14B 0.05 ppm | Co GE_IMS14B 0.1 ppm | Cr GE_IMS14B 1 ppm | Cu GE_IMS14B 0.5 ppm | Fe GE_IMS14B 0.01 % | Ga GE_IMS14B 0.1 ppm | Hg GE_IMS14B 0.01 ppm |
|--|--------------------------------|--------------------------------|-------------------------------|-----------------------------|-------------------------------|------------------------------|-------------------------------|--------------------------------|
| B00312935 | 0.16 | 25.6 | 3.0 | 23 | 22.2 | 1.53 | 2.7 | <0.01 |
| B00312936 | 0.10 | 31.0 | 3.0 | 26 | 22.1 | 1.72 | 2.5 | 0.02 |
| B00312937 | 0.11 | 55.9 | 1.6 | 19 | 11.0 | 1.54 | 3.1 | <0.01 |
| B00312938 | 0.02 | 47.4 | 1.1 | 15 | 12.4 | 1.17 | 2.3 | <0.01 |
| B00312939 | 0.06 | 34.2 | 15.1 | 19 | 14.2 | 1.18 | 1.3 | <0.01 |
| B00312940 | 0.28 | 35.8 | 11.0 | 67 | 42.2 | 2.96 | 6.3 | <0.01 |
| B00312941 | 0.27 | 35.8 | 10.5 | 64 | 43.8 | 2.87 | 6.2 | <0.01 |
| B00312942 | 0.38 | 27.3 | 11.7 | 69 | 45.8 | 2.76 | 6.1 | <0.01 |
| B00312943 | 0.34 | 38.6 | 10.0 | 55 | 43.6 | 2.99 | 4.9 | <0.01 |
| B00312944 | 0.35 | 35.9 | 13.5 | 57 | 34.3 | 2.85 | 4.9 | <0.01 |
| B00312945 | 0.37 | 30.5 | 10.2 | 58 | 43.7 | 2.67 | 5.0 | <0.01 |
| B00312946 | 0.31 | 21.5 | 10.4 | 67 | 40.1 | 3.03 | 5.5 | <0.01 |
| B00312947 | 0.50 | 27.4 | 13.1 | 55 | 56.3 | 3.08 | 5.1 | <0.01 |
| B00312948 | 0.33 | 40.5 | 8.6 | 62 | 31.1 | 2.73 | 5.3 | <0.01 |
| *Rep B00312919 | 0.08 | 52.6 | 4.5 | 19 | 31.2 | 1.92 | 2.9 | <0.01 |
| *Rep B00312946 | 0.32 | 23.4 | 10.9 | 72 | 39.9 | 2.94 | 5.6 | <0.01 |
| *Std OREAS922 | 0.26 | 65.4 | 19.3 | 41 | 2220 | 5.01 | 8.2 | 0.01 |
| *Std OREAS209 | 0.08 | 27.4 | 28.3 | 41 | 79.3 | 5.99 | 4.0 | <0.01 |
| *Blk BLANK | <0.01 | <0.05 | <0.1 | <1 | <0.5 | <0.01 | <0.1 | <0.01 |
| *Blk BLANK | <0.01 | <0.05 | <0.1 | <1 | <0.5 | <0.01 | <0.1 | <0.01 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | K GE_IMS14B 0.01 % | La GE_IMS14B 0.1 ppm | Mg GE_IMS14B 0.01 % | Mn GE_IMS14B 2 ppm | Mo GE_IMS14B 0.05 ppm | Na GE_IMS14B 0.01 % | Ni GE_IMS14B 0.5 ppm | P GE_IMS14B 50 ppm |
|--|-----------------------------|-------------------------------|------------------------------|-----------------------------|--------------------------------|------------------------------|-------------------------------|-----------------------------|
| B00312896 | 0.14 | 31.4 | 0.29 | 855 | 1.28 | 0.11 | 10.6 | 840 |
| B00312897 | 0.26 | 41.3 | 0.25 | 647 | 3.35 | 0.11 | 7.8 | 580 |
| B00312898 | 0.29 | 32.7 | 0.26 | 521 | 2.06 | 0.12 | 6.3 | 630 |
| B00312899 | 0.53 | 32.5 | 0.49 | 554 | 1.84 | 0.11 | 8.3 | 1090 |
| B00312900 | 0.74 | 13.3 | 1.37 | 633 | 2.25 | 0.13 | 39.4 | 1080 |
| B00312901 | 0.93 | 24.5 | 1.04 | 710 | 1.57 | 0.13 | 15.8 | 1730 |
| B00312902 | 0.47 | 20.9 | 0.88 | 599 | 1.62 | 0.16 | 14.5 | 1600 |
| B00312903 | 1.39 | 2.2 | 2.38 | 833 | 1.42 | 0.19 | 88.3 | 910 |
| B00312904 | 1.13 | 8.6 | 2.00 | 481 | 4.56 | 0.20 | 76.4 | 800 |
| B00312905 | 0.40 | 35.7 | 0.39 | 395 | 1.71 | 0.11 | 9.9 | 490 |
| B00312906 | 0.83 | 64.9 | 1.06 | 515 | 1.46 | 0.10 | 32.2 | 380 |
| B00312907 | 0.27 | 59.7 | 0.27 | 451 | 2.33 | 0.11 | 5.3 | 300 |
| B00312908 | 0.72 | 24.1 | 1.32 | 596 | 2.03 | 0.13 | 37.4 | 720 |
| B00312909 | 0.98 | 29.9 | 1.16 | 700 | 1.81 | 0.13 | 17.9 | 1390 |
| B00312910 | 0.91 | 34.4 | 0.99 | 606 | 2.55 | 0.10 | 21.2 | 830 |
| B00312911 | 0.85 | 34.1 | 0.98 | 643 | 2.62 | 0.10 | 20.2 | 830 |
| B00312912 | 0.39 | 41.8 | 0.32 | 419 | 2.08 | 0.06 | 12.9 | 270 |
| B00312913 | 0.40 | 34.7 | 0.54 | 490 | 4.17 | 0.08 | 22.6 | 430 |
| B00312914 | 0.57 | 20.9 | 0.60 | 375 | 3.16 | 0.04 | 26.9 | 380 |
| B00312915 | 0.36 | 16.1 | 0.53 | 606 | 3.72 | 0.22 | 3.4 | 880 |
| B00312916 | 0.89 | 34.6 | 0.81 | 499 | 2.53 | 0.07 | 30.9 | 620 |
| B00312917 | 0.57 | 29.3 | 0.27 | 305 | 4.87 | 0.06 | 13.2 | 150 |
| B00312918 | 0.70 | 25.6 | 0.55 | 333 | 6.76 | 0.06 | 23.1 | 430 |
| B00312919 | 0.39 | 22.9 | 0.19 | 202 | 3.63 | 0.05 | 10.6 | 100 |
| B00312920 | 0.20 | 7.1 | 0.80 | 425 | 2.30 | 0.15 | 5.7 | 640 |
| B00312921 | 0.17 | 37.2 | 0.04 | 207 | 2.93 | 0.07 | 3.8 | <50 |
| B00312922 | 0.15 | 54.7 | 0.03 | 246 | 2.48 | 0.08 | 3.3 | <50 |
| B00312923 | 0.12 | 61.0 | 0.03 | 211 | 2.15 | 0.07 | 3.1 | <50 |
| B00312924 | 0.18 | 40.7 | 0.02 | 210 | 2.59 | 0.08 | 4.0 | <50 |
| B00312925 | 0.03 | 32.8 | 0.04 | 237 | 2.29 | 0.08 | 4.9 | <50 |
| B00312926 | 0.07 | 60.8 | 0.04 | 225 | 2.29 | 0.10 | 3.4 | 740 |
| B00312927 | 0.36 | 33.0 | 0.28 | 263 | 5.03 | 0.07 | 19.2 | 640 |
| B00312928 | 0.38 | 14.3 | 0.32 | 223 | 5.67 | 0.05 | 22.6 | 490 |
| B00312929 | 0.22 | 19.1 | 0.12 | 165 | 3.52 | 0.05 | 6.4 | 90 |
| *Dup B00312929 | 0.23 | 18.3 | 0.13 | 171 | 3.64 | 0.05 | 6.7 | 90 |
| B00312930 | 0.37 | 7.7 | 1.20 | 623 | 8.00 | 0.24 | 44.7 | 750 |
| B00312931 | 0.46 | 22.4 | 0.49 | 248 | 3.90 | 0.07 | 15.6 | 130 |
| B00312932 | 0.11 | 14.0 | 0.05 | 151 | 4.15 | 0.04 | 3.6 | <50 |
| B00312933 | 0.12 | 9.6 | 0.24 | 402 | 5.36 | 0.04 | 5.4 | <50 |
| B00312934 | 0.17 | 19.1 | 0.20 | 294 | 4.43 | 0.05 | 9.5 | 220 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element | K | La | Mg | Mn | Mo | Na | Ni | P |
|----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Method | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B |
| Det.Lim. | 0.01 | 0.1 | 0.01 | 2 | 0.05 | 0.01 | 0.5 | 50 |
| Units | % | ppm | % | ppm | ppm | % | ppm | ppm |
| B00312935 | 0.29 | 11.2 | 0.23 | 256 | 18.0 | 0.04 | 8.7 | 190 |
| B00312936 | 0.25 | 14.0 | 0.20 | 299 | 9.46 | 0.04 | 12.4 | 180 |
| B00312937 | 0.18 | 27.0 | 0.09 | 248 | 3.85 | 0.05 | 4.9 | 100 |
| B00312938 | 0.14 | 22.3 | 0.06 | 195 | 2.98 | 0.04 | 3.6 | 50 |
| B00312939 | 0.09 | 15.9 | 0.06 | 208 | 4.05 | 0.06 | 6.2 | 60 |
| B00312940 | 0.90 | 18.0 | 0.95 | 426 | 9.24 | 0.05 | 55.4 | 960 |
| B00312941 | 0.88 | 17.9 | 0.94 | 418 | 11.4 | 0.05 | 54.2 | 920 |
| B00312942 | 0.89 | 13.9 | 0.90 | 405 | 6.39 | 0.05 | 57.0 | 880 |
| B00312943 | 0.75 | 19.5 | 0.78 | 370 | 7.02 | 0.02 | 50.0 | 1000 |
| B00312944 | 0.85 | 18.4 | 0.76 | 294 | 4.63 | 0.03 | 60.6 | 890 |
| B00312945 | 0.86 | 15.0 | 0.80 | 328 | 5.64 | 0.04 | 46.8 | 870 |
| B00312946 | 0.99 | 10.4 | 0.97 | 414 | 5.18 | 0.05 | 50.1 | 990 |
| B00312947 | 0.86 | 13.5 | 0.82 | 429 | 5.67 | 0.04 | 50.7 | 1020 |
| B00312948 | 0.80 | 20.1 | 0.84 | 275 | 4.74 | 0.05 | 46.4 | 990 |
| *Rep B00312919 | 0.40 | 23.6 | 0.19 | 206 | 3.91 | 0.06 | 10.9 | 90 |
| *Rep B00312946 | 0.97 | 11.5 | 0.94 | 402 | 5.25 | 0.05 | 51.7 | 1020 |
| *Std OREAS922 | 0.40 | 32.2 | 1.37 | 740 | 0.69 | 0.01 | 35.7 | 700 |
| *Std OREAS209 | 0.07 | 14.0 | 2.44 | 1390 | 1.86 | 0.20 | 111 | 1770 |
| *Blk BLANK | <0.01 | <0.1 | <0.01 | <2 | <0.05 | <0.01 | <0.5 | <50 |
| *Blk BLANK | <0.01 | <0.1 | <0.01 | <2 | <0.05 | <0.01 | <0.5 | <50 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | Pb | Rb | Sb | Sc | Sn | Sr | Th | Ti |
|--|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B |
| | 0.2 | 0.2 | 0.05 | 0.1 | 0.3 | 0.5 | 0.1 | 0.01 |
| | ppm | ppm | ppm | ppm | ppm | ppm | ppm | % |
| B00312896 | 6.8 | 15.9 | 0.43 | 3.5 | 5.4 | 37.5 | 7.2 | 0.16 |
| B00312897 | 16.9 | 22.3 | 0.42 | 5.4 | 2.5 | 26.3 | 9.9 | 0.11 |
| B00312898 | 6.3 | 25.7 | 0.22 | 4.1 | 4.4 | 21.0 | 10.5 | 0.16 |
| B00312899 | 4.7 | 54.7 | 0.19 | 5.1 | 2.9 | 20.1 | 11.6 | 0.21 |
| B00312900 | 2.7 | 50.9 | 0.14 | 7.0 | 1.8 | 33.3 | 4.7 | 0.34 |
| B00312901 | 5.7 | 70.4 | 0.09 | 7.1 | 2.6 | 42.4 | 5.7 | 0.30 |
| B00312902 | 5.0 | 35.7 | 0.07 | 7.6 | 2.3 | 35.2 | 4.3 | 0.30 |
| B00312903 | 4.7 | 150 | 0.07 | 8.7 | 2.6 | 53.6 | 0.7 | 0.27 |
| B00312904 | 4.2 | 79.3 | 0.07 | 6.1 | 1.7 | 35.3 | 4.1 | 0.26 |
| B00312905 | 6.2 | 40.9 | 0.17 | 2.5 | 4.4 | 13.2 | 18.6 | 0.13 |
| B00312906 | 5.2 | 61.3 | 0.11 | 4.3 | 3.1 | 23.6 | 11.9 | 0.21 |
| B00312907 | 6.6 | 23.8 | 0.19 | 3.5 | 3.8 | 17.4 | 16.6 | 0.10 |
| B00312908 | 4.5 | 52.0 | 0.11 | 5.8 | 2.9 | 29.0 | 8.2 | 0.30 |
| B00312909 | 4.8 | 76.6 | 0.09 | 6.0 | 3.3 | 34.9 | 9.6 | 0.35 |
| B00312910 | 4.3 | 73.7 | 0.07 | 5.4 | 3.4 | 26.9 | 12.3 | 0.27 |
| B00312911 | 4.4 | 68.0 | 0.06 | 5.7 | 3.5 | 30.4 | 11.6 | 0.29 |
| B00312912 | 4.4 | 40.3 | 0.14 | 2.7 | 2.7 | 25.2 | 15.7 | 0.09 |
| B00312913 | 5.8 | 35.4 | 0.24 | 3.1 | 2.7 | 38.4 | 12.5 | 0.07 |
| B00312914 | 6.6 | 43.5 | 0.21 | 3.0 | 1.1 | 36.5 | 13.9 | 0.09 |
| B00312915 | 9.1 | 32.1 | 0.20 | 2.2 | 0.7 | 96.5 | 13.0 | 0.09 |
| B00312916 | 7.0 | 68.7 | 0.16 | 4.8 | 1.9 | 70.2 | 13.6 | 0.18 |
| B00312917 | 3.2 | 50.3 | 0.06 | 2.1 | 1.2 | 6.7 | 20.4 | 0.08 |
| B00312918 | 2.1 | 61.1 | <0.05 | 4.7 | 2.2 | 17.3 | 11.8 | 0.13 |
| B00312919 | 3.3 | 28.2 | 0.06 | 1.4 | 1.1 | 6.5 | 21.7 | 0.05 |
| B00312920 | 3.2 | 6.9 | 0.06 | 2.6 | 0.3 | 66.5 | 2.9 | 0.13 |
| B00312921 | 6.8 | 18.8 | 0.05 | 0.9 | 3.4 | 5.4 | 20.7 | 0.02 |
| B00312922 | 7.7 | 14.3 | <0.05 | 1.1 | 4.7 | 5.9 | 22.8 | 0.03 |
| B00312923 | 7.3 | 7.4 | <0.05 | 1.2 | 4.2 | 8.6 | 24.3 | 0.02 |
| B00312924 | 11.9 | 19.6 | 0.08 | 0.9 | 4.8 | 3.6 | 23.9 | 0.03 |
| B00312925 | 2.8 | 3.6 | 0.07 | 0.9 | 2.6 | 15.5 | 18.7 | 0.03 |
| B00312926 | 4.1 | 5.1 | 0.06 | 1.2 | 2.7 | 18.0 | 22.9 | 0.03 |
| B00312927 | 4.9 | 41.8 | 0.23 | 2.7 | 2.3 | 22.8 | 17.4 | 0.05 |
| B00312928 | 8.9 | 57.1 | 0.08 | 2.5 | 1.0 | 14.2 | 18.5 | 0.04 |
| B00312929 | 6.4 | 27.4 | <0.05 | 1.8 | 1.1 | 10.2 | 21.5 | 0.02 |
| *Dup B00312929 | 6.5 | 27.3 | 0.06 | 1.7 | 1.3 | 10.9 | 20.5 | 0.02 |
| B00312930 | 39.5 | 14.0 | 4.01 | 4.2 | 0.8 | 93.2 | 4.1 | 0.18 |
| B00312931 | 7.3 | 53.7 | 0.17 | 1.9 | 1.1 | 13.7 | 19.8 | 0.04 |
| B00312932 | 8.1 | 8.6 | 0.48 | 1.0 | 0.8 | 4.7 | 20.3 | <0.01 |
| B00312933 | 8.1 | 7.3 | 3.40 | 1.5 | 0.5 | 22.8 | 23.5 | <0.01 |
| B00312934 | 7.8 | 17.8 | 0.54 | 2.4 | 0.8 | 17.0 | 19.7 | 0.01 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | Pb GE_IMS14B 0.2 ppm | Rb GE_IMS14B 0.2 ppm | Sb GE_IMS14B 0.05 ppm | Sc GE_IMS14B 0.1 ppm | Sn GE_IMS14B 0.3 ppm | Sr GE_IMS14B 0.5 ppm | Th GE_IMS14B 0.1 ppm | Ti GE_IMS14B 0.01 % |
|--|-------------------------------|-------------------------------|--------------------------------|-------------------------------|-------------------------------|-------------------------------|-------------------------------|------------------------------|
| B00312935 | 8.7 | 27.0 | 0.18 | 2.3 | 1.3 | 11.5 | 19.3 | 0.05 |
| B00312936 | 7.6 | 28.6 | 0.40 | 2.8 | 1.4 | 13.9 | 19.5 | 0.02 |
| B00312937 | 7.1 | 25.0 | 0.42 | 2.4 | 3.2 | 10.3 | 20.3 | 0.02 |
| B00312938 | 6.0 | 17.8 | 0.33 | 1.9 | 2.1 | 5.1 | 21.4 | <0.01 |
| B00312939 | 6.9 | 8.6 | 0.24 | 1.4 | 1.0 | 10.3 | 20.2 | <0.01 |
| B00312940 | 5.2 | 72.1 | 0.85 | 5.5 | 0.9 | 28.8 | 7.7 | 0.07 |
| B00312941 | 5.4 | 69.7 | 0.74 | 5.4 | 0.8 | 28.9 | 7.7 | 0.07 |
| B00312942 | 4.2 | 67.7 | 2.62 | 4.4 | 1.4 | 29.1 | 5.7 | 0.11 |
| B00312943 | 7.1 | 64.2 | 1.56 | 3.2 | 0.9 | 13.5 | 8.0 | 0.08 |
| B00312944 | 7.5 | 65.0 | 2.25 | 3.5 | 1.2 | 17.3 | 7.1 | 0.10 |
| B00312945 | 4.3 | 63.2 | 0.65 | 3.4 | 2.6 | 12.6 | 6.0 | 0.12 |
| B00312946 | 3.6 | 63.8 | 0.35 | 3.9 | 1.3 | 11.0 | 5.1 | 0.16 |
| B00312947 | 5.4 | 58.8 | 2.45 | 3.4 | 2.0 | 14.7 | 5.2 | 0.12 |
| B00312948 | 5.0 | 60.2 | 1.72 | 3.6 | 1.4 | 13.7 | 8.0 | 0.10 |
| *Rep B00312919 | 3.1 | 29.0 | 0.06 | 1.5 | 1.1 | 6.2 | 21.4 | 0.05 |
| *Rep B00312946 | 3.8 | 65.0 | 0.36 | 4.1 | 1.4 | 10.8 | 5.3 | 0.16 |
| *Std OREAS922 | 57.8 | 25.4 | 0.53 | 3.2 | 3.9 | 14.2 | 15.1 | 0.13 |
| *Std OREAS209 | 3.3 | 4.1 | 1.10 | 3.5 | 0.9 | 62.4 | 1.7 | 0.14 |
| *Blk BLANK | <0.2 | <0.2 | <0.05 | <0.1 | <0.3 | <0.5 | <0.1 | <0.01 |
| *Blk BLANK | <0.2 | <0.2 | <0.05 | <0.1 | <0.3 | <0.5 | <0.1 | <0.01 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | TI | U | V | W | Y | Zn |
|--|-----------|-----------|-----------|-----------|-----------|-----------|
| | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B | GE_IMS14B |
| | 0.02 | 0.05 | 1 | 0.1 | 0.05 | 1 |
| | ppm | ppm | ppm | ppm | ppm | ppm |
| B00312896 | 0.10 | 1.57 | 37 | 3.4 | 27.6 | 72 |
| B00312897 | 0.16 | 1.70 | 23 | 2.1 | 31.6 | 67 |
| B00312898 | 0.17 | 2.10 | 20 | 3.6 | 29.0 | 57 |
| B00312899 | 0.33 | 2.20 | 41 | 2.0 | 28.7 | 65 |
| B00312900 | 0.28 | 1.01 | 69 | 0.5 | 17.2 | 57 |
| B00312901 | 0.44 | 1.00 | 58 | 1.1 | 29.8 | 96 |
| B00312902 | 0.25 | 0.94 | 59 | 1.0 | 30.7 | 67 |
| B00312903 | 1.26 | 0.42 | 100 | 0.4 | 13.4 | 124 |
| B00312904 | 0.49 | 0.81 | 60 | 0.7 | 14.0 | 52 |
| B00312905 | 0.23 | 2.93 | 17 | 3.9 | 37.9 | 58 |
| B00312906 | 0.38 | 1.46 | 43 | 1.6 | 23.5 | 73 |
| B00312907 | 0.17 | 2.97 | 18 | 2.0 | 32.4 | 51 |
| B00312908 | 0.33 | 1.65 | 62 | 2.9 | 24.1 | 61 |
| B00312909 | 0.51 | 1.54 | 84 | 0.7 | 27.0 | 81 |
| B00312910 | 0.46 | 2.59 | 64 | 1.9 | 29.7 | 71 |
| B00312911 | 0.43 | 2.47 | 64 | 2.0 | 31.2 | 75 |
| B00312912 | 0.26 | 3.23 | 22 | 2.1 | 34.5 | 58 |
| B00312913 | 0.26 | 2.67 | 40 | 1.5 | 24.7 | 79 |
| B00312914 | 0.28 | 2.35 | 39 | 2.3 | 17.0 | 69 |
| B00312915 | 0.28 | 2.51 | 26 | 1.9 | 17.0 | 66 |
| B00312916 | 0.51 | 2.07 | 38 | 0.9 | 16.0 | 53 |
| B00312917 | 0.38 | 4.08 | 14 | 3.1 | 30.0 | 38 |
| B00312918 | 0.40 | 2.72 | 43 | 7.0 | 19.0 | 50 |
| B00312919 | 0.21 | 6.54 | 9 | 3.5 | 27.8 | 27 |
| B00312920 | 0.04 | 0.88 | 106 | 2.6 | 5.02 | 37 |
| B00312921 | 0.15 | 4.62 | 2 | 4.5 | 29.7 | 35 |
| B00312922 | 0.11 | 5.07 | 2 | 3.8 | 29.6 | 41 |
| B00312923 | 0.04 | 4.57 | 2 | 3.0 | 29.5 | 29 |
| B00312924 | 0.16 | 5.20 | <1 | 4.3 | 34.3 | 46 |
| B00312925 | 0.02 | 2.87 | 8 | 2.7 | 25.1 | 18 |
| B00312926 | 0.03 | 4.23 | 5 | 4.0 | 32.9 | 23 |
| B00312927 | 0.31 | 4.74 | 46 | 4.2 | 28.6 | 45 |
| B00312928 | 0.43 | 8.91 | 42 | 6.7 | 33.9 | 38 |
| B00312929 | 0.17 | 8.00 | 8 | 7.4 | 28.8 | 29 |
| *Dup B00312929 | 0.18 | 8.03 | 8 | 7.0 | 28.9 | 29 |
| B00312930 | 0.10 | 1.00 | 122 | 21.4 | 6.48 | 73 |
| B00312931 | 0.38 | 7.36 | 14 | 7.6 | 20.0 | 31 |
| B00312932 | 0.09 | 9.08 | 1 | 4.9 | 18.6 | 32 |
| B00312933 | 0.14 | 11.8 | 3 | 3.4 | 15.9 | 31 |
| B00312934 | 0.13 | 7.33 | 12 | 3.2 | 17.6 | 46 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

| Element Method Det.Lim. Units | Tl GE_IMS14B 0.02 ppm | U GE_IMS14B 0.05 ppm | V GE_IMS14B 1 ppm | W GE_IMS14B 0.1 ppm | Y GE_IMS14B 0.05 ppm | Zn GE_IMS14B 1 ppm |
|--|--------------------------------|-------------------------------|----------------------------|------------------------------|-------------------------------|-----------------------------|
| B00312935 | 0.18 | 9.42 | 14 | 5.0 | 26.2 | 28 |
| B00312936 | 0.26 | 10.3 | 20 | 2.9 | 26.3 | 33 |
| B00312937 | 0.14 | 7.25 | 5 | 3.2 | 31.2 | 33 |
| B00312938 | 0.12 | 8.57 | 2 | 2.3 | 31.9 | 25 |
| B00312939 | 0.08 | 7.31 | 5 | 102 | 25.4 | 17 |
| B00312940 | 0.55 | 3.24 | 102 | 3.3 | 16.3 | 80 |
| B00312941 | 0.55 | 3.37 | 99 | 1.8 | 16.2 | 78 |
| B00312942 | 0.49 | 2.05 | 90 | 8.1 | 10.3 | 83 |
| B00312943 | 0.45 | 2.39 | 73 | 2.1 | 16.9 | 86 |
| B00312944 | 0.46 | 3.58 | 80 | 2.4 | 15.0 | 83 |
| B00312945 | 0.49 | 2.00 | 77 | 8.0 | 11.6 | 87 |
| B00312946 | 0.43 | 1.68 | 88 | 5.6 | 9.71 | 82 |
| B00312947 | 0.47 | 2.59 | 78 | 3.9 | 11.2 | 101 |
| B00312948 | 0.45 | 2.03 | 84 | 2.7 | 15.3 | 61 |
| *Rep B00312919 | 0.21 | 6.36 | 9 | 3.6 | 28.3 | 27 |
| *Rep B00312946 | 0.45 | 1.88 | 94 | 5.3 | 10.6 | 86 |
| *Std OREAS922 | 0.15 | 2.08 | 29 | 1.3 | 17.2 | 256 |
| *Std OREAS209 | 0.04 | 0.46 | 40 | 0.2 | 13.3 | 77 |
| *Blk BLANK | <0.02 | <0.05 | <1 | <0.1 | <0.05 | <1 |
| *Blk BLANK | <0.02 | <0.05 | <1 | <0.1 | <0.05 | <1 |

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .