



Certificate of Analysis
Work Order : VC162621
[Report File No.: 0000018901]

Date: September 08, 2016

To: Kendra Johnston
INDEPENDENCE GOLD CORP.
1410-650 WEST GEORGIA ST
VACOUVER BC V6B 4N8

P.O. No.: Boulevard-YK16-BLVD17
Project No.: IGO YUKON
Samples: 53
Received: Aug 22, 2016
Pages: Page 1 to 11
(Inclusive of Cover Sheet)

Methods Summary

<u>No. Of Samples</u>	<u>Method Code</u>	<u>Description</u>
53	G_LOG02	Pre-preparation processing, sorting, logging, boxing
53	G_WGH79	Weighing of samples and reporting of weights
49	G_PRP89	Weigh, dry, (up to 3.0 kg) crush to 75% passing 2 mm, split 250 g, pulverize to
53	GE_FAA313	@Au, FAS, AAS, 30g-5ml(Final Mode)
53	GE_IMS14	Aqua Regia digestion

Storage: Pulp & Reject

REJECT STORAGE : RETURN AFTER 30 DAYS
PULP STORAGE : RETURN AFTER 90 DAYS

Certified By : _____

John Chiang
QC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method

M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Methods marked with an asterisk (e.g. *NAA08V) were subcontracted

Elements marked with the @ symbol (e.g. @Cu) denote assays performed using accredited test methods

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
E00004610	2.320	<5	0.04	2.52	6	375	0.03	0.26
E00004611	1.785	<5	0.04	2.35	6	367	0.03	0.22
E00004612	2.490	<5	0.16	2.51	9	651	0.05	0.41
E00004613	2.645	<5	0.10	2.76	19	362	0.05	0.28
E00004614	2.140	10	0.09	1.85	269	307	0.09	0.29
E00004615	2.900	6	0.04	2.54	7	365	<0.02	0.50
E00004616	3.120	<5	0.05	2.00	2	364	0.03	1.12
E00004617	2.770	<5	0.05	2.20	2	312	0.02	0.68
E00004618	3.040	<5	0.03	1.39	3	100	0.08	1.86
E00004619	2.850	<5	0.04	2.05	3	292	0.04	1.26
E00004620	0.110	<5	0.06	1.35	<1	115	0.04	0.82
E00004621	2.900	<5	0.04	2.18	2	414	0.04	0.65
E00004622	3.415	<5	0.05	2.25	4	390	0.06	1.67
E00004623	2.965	<5	0.04	2.82	<1	490	0.03	1.35
E00004624	2.920	<5	0.10	1.61	2	286	0.07	1.81
E00004625	2.695	<5	0.07	2.62	3	628	0.07	1.48
E00004626	2.825	<5	0.05	3.21	2	540	0.03	1.44
E00004627	2.945	<5	0.07	2.37	14	341	<0.02	1.08
E00004628	2.650	<5	0.04	2.72	1	384	0.02	0.89
E00004629	2.535	6	0.05	2.32	<1	239	0.02	0.77
E00004630	0.110	5300	0.76	2.21	35	176	0.32	1.23
E00004631	2.475	69	0.03	2.42	2	256	<0.02	0.73
E00004632	2.425	<5	0.03	2.43	9	385	0.02	0.47
E00004633	2.950	<5	0.09	1.95	<1	358	0.03	1.56
E00004634	3.110	<5	0.08	1.17	<1	139	0.03	1.35
E00004635	2.975	<5	0.14	2.24	<1	60	0.06	2.16
E00004636	2.160	<5	0.06	0.49	9	28	0.06	0.50
E00004637	2.500	<5	0.04	0.27	16	46	0.08	0.37
E00004638	2.860	<5	0.05	0.38	11	49	0.05	0.19
E00004639	3.005	<5	0.04	0.42	6	57	0.05	0.26
E00004640	2.515	<5	0.03	0.28	7	34	0.05	0.15
E00004641	2.230	<5	0.02	0.27	7	34	0.05	0.14
E00004642	2.360	<5	0.03	0.31	10	47	0.05	0.04
E00004643	2.385	<5	0.03	0.34	61	60	0.04	0.04
E00004644	2.820	<5	0.03	0.29	53	56	0.03	0.07
*Dup E00004644	N.A.	<5	0.02	0.36	50	66	0.03	0.07
E00004645	2.460	<5	0.03	0.32	71	64	0.03	0.05
E00004646	2.695	<5	0.04	0.28	119	63	0.03	0.05
E00004647	2.740	<5	0.04	0.34	53	60	0.02	0.39
E00004648	2.395	<5	0.04	0.27	12	34	<0.02	0.29

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
E00004649	2.685	<5	0.06	1.29	26	76	0.04	1.20
E00004650	0.115	<5	0.23	1.35	<1	116	0.04	0.82
E00004651	2.725	<5	0.07	1.34	2	40	0.06	1.47
E00004652	2.985	<5	0.21	1.49	<1	25	0.21	2.16
E00004653	3.120	<5	0.08	1.29	3	112	0.08	1.08
E00004654	2.655	<5	0.02	2.29	1	168	0.02	1.32
E00004655	2.200	<5	0.05	2.00	<1	193	0.03	1.33
E00004656	3.055	<5	0.08	1.10	<1	64	0.04	1.55
E00004657	3.340	<5	0.06	1.85	<1	279	<0.02	1.73
E00004658	2.870	<5	0.04	1.38	<1	784	0.03	1.82
E00004659	2.420	<5	0.08	1.99	<1	656	0.05	1.70
E00004660	0.110	5270	0.69	2.22	36	170	0.30	1.20
E00004661	2.455	<5	0.09	2.19	<1	164	0.06	1.61
E00004662	2.195	<5	0.06	2.04	<1	131	0.03	1.78
*Rep E00004610		<5						
*Rep E00004656		<5						
*Std OREAS151B		68						
*Std OXB130		124						
*Std OXH97		1360						
*Blk BLANK		<5						
*Rep E00004611			0.04	2.32	6	366	0.03	0.22
*Rep E00004638			0.05	0.37	10	45	0.05	0.18
*Rep E00004660			0.66	2.22	35	173	0.30	1.18
*Std OREAS209			0.27	1.14	1090	72	0.05	1.43
*Std OREAS922			0.75	2.73	5	67	10.1	0.34
*Blk BLANK			<0.01	<0.01	<1	<5	<0.02	<0.01
*Blk BLANK			<0.01	<0.01	<1	<5	<0.02	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd GE_IMS14B 0.01 ppm	Ce GE_IMS14B 0.05 ppm	Co GE_IMS14B 0.1 ppm	Cr GE_IMS14B 1 ppm	Cu GE_IMS14B 0.5 ppm	Fe GE_IMS14B 0.01 %	Ga GE_IMS14B 0.1 ppm	Hg GE_IMS14B 0.01 ppm
E00004610	0.04	63.0	20.6	69	36.8	4.12	7.2	<0.01
E00004611	0.04	64.4	19.2	69	35.1	3.41	6.7	<0.01
E00004612	0.03	44.9	10.7	82	74.3	4.52	7.9	0.01
E00004613	0.05	75.8	22.0	119	57.5	4.95	8.7	0.01
E00004614	0.10	89.8	28.2	65	54.2	4.71	5.9	0.03
E00004615	0.02	42.0	16.8	62	26.5	4.04	7.1	<0.01
E00004616	0.05	27.6	15.7	84	29.1	3.49	7.2	0.02
E00004617	0.04	21.7	17.8	75	29.5	3.53	6.9	0.03
E00004618	0.05	30.5	7.4	38	15.9	1.80	5.3	0.03
E00004619	0.04	23.4	15.6	66	29.9	3.62	6.7	0.02
E00004620	0.06	14.6	8.1	14	58.4	2.58	4.1	0.02
E00004621	0.03	26.4	19.9	115	26.8	3.64	6.8	0.02
E00004622	0.07	29.6	28.7	111	52.3	3.95	7.0	<0.01
E00004623	0.04	25.7	28.5	136	34.8	4.54	8.5	<0.01
E00004624	0.08	21.1	28.4	101	70.5	3.10	5.0	<0.01
E00004625	0.09	24.3	33.5	125	56.1	5.28	8.4	0.01
E00004626	0.03	41.1	28.4	157	29.4	5.06	9.7	<0.01
E00004627	0.03	24.6	19.1	77	34.1	3.83	7.6	<0.01
E00004628	0.02	21.0	20.7	92	30.9	4.42	8.3	<0.01
E00004629	0.01	38.5	16.7	63	26.5	3.86	7.2	0.01
E00004630	0.14	16.6	15.8	99	96.8	4.10	6.2	0.29
E00004631	<0.01	14.7	14.5	49	20.7	3.18	6.5	<0.01
E00004632	0.03	38.5	17.1	81	28.4	3.73	7.3	<0.01
E00004633	0.05	16.5	22.3	172	100.0	2.20	4.4	<0.01
E00004634	0.06	7.55	14.7	96	72.0	1.27	2.7	0.02
E00004635	0.14	4.48	32.5	170	74.1	2.33	3.8	<0.01
E00004636	0.05	15.4	5.8	48	32.5	1.48	1.8	<0.01
E00004637	0.04	27.9	1.4	13	30.3	0.67	1.0	<0.01
E00004638	0.01	24.9	2.2	25	37.2	1.11	1.7	0.01
E00004639	0.02	30.3	2.6	20	20.6	1.21	2.2	0.01
E00004640	0.01	27.5	1.2	15	13.1	0.81	1.3	0.02
E00004641	0.02	26.5	1.2	15	11.4	0.78	1.3	<0.01
E00004642	0.02	27.8	2.2	19	9.8	0.94	1.4	0.02
E00004643	0.02	29.0	2.3	20	20.5	1.24	1.4	0.02
E00004644	0.02	26.3	1.5	15	12.8	0.90	1.2	0.02
*Dup E00004644	0.02	25.7	2.4	18	13.5	1.13	1.6	0.01
E00004645	0.03	29.6	2.1	20	21.9	1.24	1.3	0.02
E00004646	0.04	32.2	1.6	13	25.3	1.15	0.9	<0.01
E00004647	0.06	28.0	3.0	16	13.6	1.53	1.2	<0.01
E00004648	0.03	18.6	2.0	26	18.7	1.19	1.1	0.02

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd GE_IMS14B 0.01 ppm	Ce GE_IMS14B 0.05 ppm	Co GE_IMS14B 0.1 ppm	Cr GE_IMS14B 1 ppm	Cu GE_IMS14B 0.5 ppm	Fe GE_IMS14B 0.01 %	Ga GE_IMS14B 0.1 ppm	Hg GE_IMS14B 0.01 ppm
E00004649	0.05	5.11	20.3	178	47.7	1.54	2.8	<0.01
E00004650	0.05	14.4	8.3	14	61.6	2.63	4.1	0.05
E00004651	0.04	2.89	17.5	83	37.1	2.15	3.5	0.01
E00004652	0.10	4.33	20.2	14	72.3	3.74	5.8	0.03
E00004653	0.06	21.2	14.9	65	34.7	2.21	4.3	<0.01
E00004654	0.03	4.73	32.1	288	17.7	2.47	3.7	<0.01
E00004655	0.11	11.1	21.6	161	47.4	1.76	3.5	<0.01
E00004656	0.05	1.58	15.0	107	71.2	1.44	2.6	0.05
E00004657	0.04	0.66	21.9	183	62.2	1.61	2.8	0.01
E00004658	0.07	4.59	16.6	106	38.7	1.45	2.7	0.06
E00004659	0.04	0.90	23.9	142	41.9	1.63	3.1	<0.01
E00004660	0.13	16.4	15.4	95	97.8	4.25	6.2	0.29
E00004661	0.05	1.20	21.1	163	59.8	1.82	3.3	0.08
E00004662	0.03	0.32	19.7	244	44.2	1.67	2.9	0.16
*Rep E00004611	0.03	63.4	18.8	62	34.1	3.35	6.6	<0.01
*Rep E00004638	0.02	25.0	2.1	24	36.0	1.10	1.7	<0.01
*Rep E00004660	0.15	16.2	15.7	97	99.1	4.25	6.3	0.32
*Std OREAS209	0.08	27.3	28.8	40	74.1	5.59	3.7	<0.01
*Std OREAS922	0.28	68.0	18.5	42	2170	4.88	7.6	0.02
*Blk BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01
*Blk BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K GE_IMS14B 0.01 %	La GE_IMS14B 0.1 ppm	Mg GE_IMS14B 0.01 %	Mn GE_IMS14B 2 ppm	Mo GE_IMS14B 0.05 ppm	Na GE_IMS14B 0.01 %	Ni GE_IMS14B 0.5 ppm	P GE_IMS14B 50 ppm
E00004610	1.20	25.8	1.28	575	2.96	0.06	45.3	250
E00004611	1.16	26.0	1.24	457	2.21	0.06	40.5	270
E00004612	1.34	26.2	1.56	523	5.39	0.09	33.1	370
E00004613	1.05	40.3	1.64	684	3.35	0.06	64.9	470
E00004614	0.95	45.6	1.00	721	2.17	0.04	81.7	290
E00004615	1.53	21.8	1.17	563	3.12	0.08	42.2	430
E00004616	1.15	13.9	1.05	505	2.53	0.08	42.4	760
E00004617	1.34	10.8	1.23	584	2.48	0.08	44.9	750
E00004618	0.31	14.0	0.51	263	3.04	0.06	19.3	1020
E00004619	1.20	11.8	1.05	685	2.72	0.08	38.7	550
E00004620	0.21	6.8	0.60	327	2.66	0.17	6.5	750
E00004621	1.32	13.5	1.30	521	2.11	0.09	72.9	530
E00004622	0.93	14.6	1.20	709	4.75	0.11	99.1	1470
E00004623	1.10	12.6	1.56	806	2.87	0.12	89.1	1200
E00004624	0.51	10.1	1.02	586	7.64	0.12	92.9	1760
E00004625	1.11	12.9	1.42	896	8.16	0.16	84.1	880
E00004626	1.53	21.5	2.10	818	5.15	0.12	88.9	1020
E00004627	1.43	12.6	1.51	593	2.77	0.10	47.4	740
E00004628	1.59	10.7	1.46	740	4.78	0.10	51.6	760
E00004629	1.29	20.2	1.23	502	2.44	0.10	37.5	580
E00004630	0.38	7.9	1.15	587	7.11	0.26	41.5	790
E00004631	1.42	7.5	1.27	499	1.86	0.09	31.7	640
E00004632	1.32	19.9	1.33	449	3.42	0.09	49.1	490
E00004633	0.68	9.3	1.84	338	3.62	0.15	92.7	420
E00004634	0.28	4.2	1.12	231	2.16	0.11	59.2	270
E00004635	0.24	2.5	2.86	394	3.17	0.13	165	120
E00004636	0.17	7.4	0.26	187	8.34	0.08	38.4	50
E00004637	0.21	15.1	0.04	128	3.89	0.06	4.0	110
E00004638	0.24	13.1	0.05	173	7.66	0.09	8.3	80
E00004639	0.26	16.1	0.06	163	6.79	0.09	7.9	90
E00004640	0.19	14.8	0.04	78	4.88	0.06	4.2	80
E00004641	0.18	14.2	0.03	75	4.61	0.06	4.0	80
E00004642	0.23	14.7	0.02	100	8.31	0.07	7.5	100
E00004643	0.25	15.9	0.03	213	7.81	0.08	8.0	90
E00004644	0.19	13.6	0.04	161	3.99	0.06	5.3	80
*Dup E00004644	0.23	13.2	0.04	200	4.13	0.08	7.7	90
E00004645	0.21	15.4	0.03	236	4.72	0.07	7.5	100
E00004646	0.23	17.1	0.04	260	3.70	0.05	6.1	100
E00004647	0.27	14.8	0.17	386	4.55	0.07	10.8	90
E00004648	0.22	9.1	0.12	201	6.79	0.08	9.0	<50

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K GE_IMS14B 0.01 %	La GE_IMS14B 0.1 ppm	Mg GE_IMS14B 0.01 %	Mn GE_IMS14B 2 ppm	Mo GE_IMS14B 0.05 ppm	Na GE_IMS14B 0.01 %	Ni GE_IMS14B 0.5 ppm	P GE_IMS14B 50 ppm
E00004649	0.18	2.5	1.41	237	5.11	0.12	141	120
E00004650	0.21	6.7	0.61	328	2.83	0.16	6.5	740
E00004651	0.10	1.3	1.18	379	5.96	0.16	64.3	270
E00004652	0.09	1.8	1.03	639	6.32	0.28	13.6	580
E00004653	0.30	11.4	1.04	356	2.78	0.12	45.4	370
E00004654	0.12	2.5	4.13	272	2.07	0.16	238	80
E00004655	0.30	6.0	2.48	274	4.23	0.16	155	240
E00004656	0.07	0.8	1.11	237	3.62	0.13	48.1	250
E00004657	0.30	0.3	1.94	254	2.30	0.15	123	110
E00004658	0.09	2.3	1.49	248	3.00	0.12	78.4	60
E00004659	0.34	0.4	1.98	266	2.25	0.14	123	180
E00004660	0.36	8.0	1.12	568	7.19	0.25	42.0	770
E00004661	0.30	0.5	2.00	293	3.21	0.14	124	160
E00004662	0.09	0.1	2.07	273	3.62	0.12	137	60
*Rep E00004611	1.15	25.3	1.22	447	2.00	0.06	39.9	250
*Rep E00004638	0.24	13.1	0.05	170	7.28	0.09	8.3	70
*Rep E00004660	0.36	7.8	1.12	568	7.16	0.25	42.3	760
*Std OREAS209	0.08	14.2	2.39	1330	1.89	0.19	110	1780
*Std OREAS922	0.41	33.1	1.36	740	0.75	0.03	33.1	740
*Blk BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50
*Blk BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
E00004610	3.3	41.5	0.06	7.5	0.4	18.3	8.4	0.11
E00004611	3.3	41.6	0.06	7.0	<0.3	15.4	8.6	0.11
E00004612	2.8	41.7	0.10	8.2	0.4	47.9	5.1	0.18
E00004613	3.1	37.9	0.14	10.0	0.4	23.0	8.8	0.09
E00004614	4.0	41.4	2.78	8.0	<0.3	17.7	10.4	0.07
E00004615	1.9	64.6	0.09	5.4	0.5	24.0	6.9	0.20
E00004616	2.8	43.2	0.07	5.6	0.5	73.5	3.9	0.24
E00004617	2.5	52.7	0.07	5.0	0.4	53.2	3.1	0.24
E00004618	3.3	14.1	0.09	3.0	0.8	144	3.6	0.29
E00004619	2.6	52.7	0.05	4.7	0.5	53.4	3.5	0.26
E00004620	3.6	7.2	0.07	2.1	<0.3	62.5	2.2	0.12
E00004621	1.8	50.3	0.05	5.7	0.5	34.3	3.6	0.23
E00004622	3.1	33.9	0.06	7.5	0.7	70.7	2.9	0.41
E00004623	1.9	41.1	<0.05	8.7	0.7	44.4	3.5	0.36
E00004624	2.9	25.2	0.08	5.8	0.6	63.5	2.3	0.40
E00004625	3.4	45.7	0.08	11.1	0.6	46.8	2.7	0.40
E00004626	2.3	62.9	<0.05	9.7	0.6	40.7	5.1	0.28
E00004627	1.9	57.0	0.07	6.0	0.5	35.9	3.8	0.26
E00004628	2.3	63.5	0.05	6.5	0.6	46.1	2.9	0.30
E00004629	2.6	59.9	<0.05	5.0	0.5	34.7	6.9	0.21
E00004630	43.0	13.5	3.81	4.3	0.8	94.0	3.6	0.19
E00004631	1.4	61.0	<0.05	3.9	0.3	26.4	2.4	0.22
E00004632	2.3	56.9	<0.05	5.9	0.6	28.9	6.9	0.15
E00004633	1.5	37.5	0.05	5.0	0.5	44.4	2.9	0.11
E00004634	1.1	19.5	0.07	4.1	0.3	28.6	1.6	0.07
E00004635	1.2	20.6	0.08	6.0	0.5	34.0	0.9	0.05
E00004636	12.9	9.9	0.18	2.5	0.7	13.9	11.1	<0.01
E00004637	20.0	13.8	0.28	0.7	0.4	7.8	13.9	<0.01
E00004638	22.1	13.1	0.38	1.3	1.0	9.9	14.2	<0.01
E00004639	21.6	14.3	0.58	1.4	1.0	11.7	14.4	<0.01
E00004640	19.6	10.5	0.33	1.4	1.0	6.4	14.5	<0.01
E00004641	18.8	10.3	0.80	1.3	0.9	6.2	14.2	<0.01
E00004642	18.0	13.4	0.61	1.2	0.8	6.1	14.1	<0.01
E00004643	20.8	14.0	0.69	1.2	0.8	7.2	13.7	<0.01
E00004644	24.5	11.4	0.58	1.3	0.5	7.4	14.3	<0.01
*Dup E00004644	23.6	13.0	0.50	1.3	0.6	8.3	14.2	<0.01
E00004645	24.1	13.2	0.58	1.2	0.6	9.0	14.7	<0.01
E00004646	29.2	14.9	0.75	1.4	0.3	10.2	13.5	<0.01
E00004647	31.7	16.7	0.41	2.1	0.4	18.3	13.9	<0.01
E00004648	15.2	13.7	0.26	0.8	0.6	15.2	12.7	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb GE_IMS14B 0.2 ppm	Rb GE_IMS14B 0.2 ppm	Sb GE_IMS14B 0.05 ppm	Sc GE_IMS14B 0.1 ppm	Sn GE_IMS14B 0.3 ppm	Sr GE_IMS14B 0.5 ppm	Th GE_IMS14B 0.1 ppm	Ti GE_IMS14B 0.01 %
E00004649	5.0	11.8	0.24	4.9	1.3	31.2	2.3	0.04
E00004650	3.9	7.3	0.06	2.1	<0.3	63.1	2.2	0.11
E00004651	3.0	6.4	0.09	6.5	1.4	34.0	0.4	0.11
E00004652	4.5	3.1	0.16	12.6	2.7	43.0	0.3	0.23
E00004653	3.8	19.9	0.20	5.5	1.4	38.9	4.3	0.09
E00004654	0.9	7.9	0.07	5.1	0.5	22.8	0.9	0.03
E00004655	1.2	20.5	0.06	4.2	0.6	27.1	2.9	0.05
E00004656	1.2	4.9	0.13	5.6	0.5	30.4	<0.1	0.09
E00004657	0.9	18.4	0.08	4.9	<0.3	39.3	<0.1	0.05
E00004658	3.6	5.7	0.09	4.4	0.4	38.4	0.9	0.10
E00004659	0.8	24.0	0.07	4.1	<0.3	43.9	<0.1	0.05
E00004660	36.9	12.7	3.33	4.0	0.7	92.3	3.5	0.18
E00004661	0.8	21.4	0.07	3.5	<0.3	34.0	<0.1	0.04
E00004662	0.6	6.4	0.06	4.0	0.4	26.3	<0.1	0.04
*Rep E00004611	3.3	40.9	0.06	6.9	<0.3	15.6	8.4	0.11
*Rep E00004638	21.7	13.0	0.34	1.2	1.0	9.8	14.3	<0.01
*Rep E00004660	37.8	12.7	3.39	4.0	0.7	93.3	3.6	0.18
*Std OREAS209	3.2	3.8	1.13	3.6	0.9	61.4	1.6	0.13
*Std OREAS922	58.5	22.3	0.46	3.1	3.7	15.5	13.7	0.12
*Blk BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01
*Blk BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	TI	U	V	W	Y	Zn
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.02	0.05	1	0.1	0.05	1
	ppm	ppm	ppm	ppm	ppm	ppm
E00004610	0.25	0.45	48	0.7	15.0	49
E00004611	0.25	0.45	46	0.7	13.9	50
E00004612	0.24	0.41	68	0.7	12.7	53
E00004613	0.28	0.68	70	0.7	20.2	61
E00004614	0.52	0.80	46	0.9	19.4	84
E00004615	0.34	0.62	46	0.9	11.5	46
E00004616	0.23	0.45	53	2.7	8.55	59
E00004617	0.27	0.39	55	3.2	6.80	56
E00004618	0.08	0.54	28	3.2	7.59	22
E00004619	0.31	0.39	56	2.4	7.60	52
E00004620	0.04	0.59	113	6.4	4.57	36
E00004621	0.30	0.43	57	1.8	8.60	61
E00004622	0.19	0.39	64	2.2	10.4	54
E00004623	0.23	0.76	85	1.0	11.2	70
E00004624	0.19	0.41	54	2.3	9.22	45
E00004625	0.33	0.43	93	0.8	13.5	85
E00004626	0.41	0.64	85	0.8	14.7	71
E00004627	0.29	0.55	55	1.7	7.58	49
E00004628	0.34	0.43	67	1.6	8.23	57
E00004629	0.32	0.64	48	1.6	9.00	52
E00004630	0.09	0.92	115	20.7	6.50	72
E00004631	0.29	0.29	37	1.2	5.59	36
E00004632	0.33	0.60	53	0.7	9.13	63
E00004633	0.29	0.40	41	0.8	3.65	24
E00004634	0.19	0.37	26	2.5	2.39	17
E00004635	0.22	0.94	35	0.4	2.87	26
E00004636	0.08	4.17	9	1.0	11.1	12
E00004637	0.11	2.13	3	0.7	9.98	20
E00004638	0.10	2.87	4	1.2	11.6	14
E00004639	0.11	5.35	6	1.4	12.4	22
E00004640	0.07	3.13	3	1.2	11.0	15
E00004641	0.07	2.98	4	1.1	10.7	15
E00004642	0.11	5.32	4	1.0	8.82	13
E00004643	0.12	5.73	5	1.1	10.9	21
E00004644	0.09	3.50	4	0.7	10.1	13
*Dup E00004644	0.10	3.48	5	0.6	9.85	13
E00004645	0.10	3.08	5	0.7	10.4	14
E00004646	0.13	2.50	4	0.8	10.3	12
E00004647	0.16	8.47	6	1.2	11.0	15
E00004648	0.12	7.52	3	1.0	10.5	9

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl GE_IMS14B 0.02 ppm	U GE_IMS14B 0.05 ppm	V GE_IMS14B 1 ppm	W GE_IMS14B 0.1 ppm	Y GE_IMS14B 0.05 ppm	Zn GE_IMS14B 1 ppm
E00004649	0.11	3.27	26	0.4	4.25	25
E00004650	0.05	0.67	114	7.2	4.73	36
E00004651	0.05	1.03	60	1.2	4.75	28
E00004652	<0.02	2.31	141	2.6	9.08	35
E00004653	0.15	5.11	51	0.9	7.00	44
E00004654	0.07	0.79	31	0.5	2.15	18
E00004655	0.17	0.76	28	0.5	2.64	22
E00004656	0.04	0.14	41	8.8	2.99	14
E00004657	0.17	0.07	31	2.8	1.61	14
E00004658	0.05	0.33	33	12.2	3.38	20
E00004659	0.27	<0.05	31	0.6	1.95	19
E00004660	0.09	0.83	110	19.8	5.88	70
E00004661	0.25	<0.05	26	11.8	1.85	18
E00004662	0.05	<0.05	27	26.9	1.33	15
*Rep E00004611	0.24	0.44	46	0.7	13.8	49
*Rep E00004638	0.09	2.85	4	1.2	11.5	14
*Rep E00004660	0.09	0.82	113	20.1	5.85	71
*Std OREAS209	0.03	0.41	41	0.3	13.1	73
*Std OREAS922	0.14	1.87	29	1.2	16.4	244
*Blk BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1
*Blk BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .