



Certificate of Analysis
Work Order : VC172168
[Report File No.: 0000023941]

Date: August 10, 2017

To: KENDRA JOHNSTON
INVOICE PAYMENT APPROVER
INDEPENDENCE GOLD CORP.
1020-625 HOWE STREET
VANCOUVER BC V6C 2T6

P.O. No.: BLVD-90403-05 / YK17_BLVD_DT1
Project No.: YK17_BLVD_DT1
Samples: 76
Received: Jul 13, 2017
Pages: Page 1 to 16
(Inclusive of Cover Sheet)

Methods Summary

<u>No. Of Samples</u>	<u>Method Code</u>	<u>Description</u>
76	G_LOG02	Pre-preparation processing, sorting, logging, boxing
76	G_WGH79	Weighing of samples and reporting of weights
76	GE_FAA313	@Au, FAS, AAS, 30g-5ml(Final Mode)
76	GE_IMS14B	Aqua Regia digestion/ICP-MS package

Storage: Pulp & Reject

REJECT STORAGE : DISPOSE AFTER 30 DAYS
PULP STORAGE : DISPOSE AFTER 90 DAYS

Certified By : _____

John Chiang
QC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method
M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Methods marked with an asterisk (e.g. *NAA08V) were subcontracted

Elements marked with the @ symbol (e.g. @Cu) denote assays performed using accredited test methods

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
1466965	0.580	<5	0.13	2.74	4	225	0.08	0.81
1466966	0.545	7	0.17	3.03	7	219	0.08	0.89
1466967	0.460	8	0.17	3.28	15	234	0.09	1.23
1466968	0.465	9	0.22	2.97	23	251	0.11	1.21
1466969	0.455	11	0.18	2.59	23	226	0.09	1.29
1466970	0.625	7	0.13	3.36	29	272	0.09	0.85
1466971	0.610	9	0.22	3.76	10	358	0.13	1.04
1466972	0.380	7	0.23	2.01	19	284	0.11	1.48
1466973	0.385	7	0.20	2.49	13	223	0.08	1.63
1466974	0.670	14	0.21	3.40	30	266	0.14	0.80
1466975	0.535	21	0.25	3.27	26	272	0.13	1.07
1466976	0.540	<5	0.16	3.51	13	311	0.11	1.04
1466977	0.495	<5	0.19	2.98	4	284	0.09	1.20
1466978	0.615	5	0.21	2.81	5	306	0.10	0.82
1466979	0.505	8	0.19	2.47	5	175	0.12	0.55
1466980	0.410	13	1.00	2.37	7	178	0.19	0.57
1466981	0.465	22	0.52	2.49	6	183	0.17	0.69
1480726	0.510	5	0.09	3.16	9	201	0.13	0.41
1480727	0.545	11	0.21	4.26	6	213	0.11	1.02
1480728	0.720	9	0.14	3.15	8	192	0.20	0.74
1480729	0.700	6	0.19	3.08	6	304	0.10	0.91
1480730	0.800	7	0.15	2.75	7	216	0.16	0.61
1480731	0.695	9	0.20	5.20	7	765	0.46	0.92
1480732	0.605	7	0.19	2.12	6	271	0.16	0.46
1480733	1.025	<5	0.07	2.78	6	190	0.17	0.50
1480734	0.825	5	0.09	2.98	8	169	0.18	0.49
1480735	0.615	<5	0.18	3.86	10	488	0.26	0.29
1480736	0.610	13	0.45	3.21	8	235	0.19	0.55
1480737	0.610	10	0.38	3.11	8	234	0.29	0.42
1480738	0.490	<5	0.25	1.43	7	258	0.17	0.23
1480739	0.650	5	0.44	2.38	8	264	0.18	0.31
1480740	0.695	<5	0.52	3.56	12	417	0.19	0.47
1481984	0.495	15	0.44	3.10	9	165	0.21	0.58
1481985	0.650	9	0.33	2.97	10	234	0.37	0.58
1481986	0.650	<5	0.22	2.17	7	294	0.34	0.44
1481987	0.670	10	0.53	2.87	14	420	0.20	0.61
1481988	0.440	10	0.96	2.98	10	414	0.22	0.53
1481989	0.845	7	0.43	2.79	8	277	0.19	0.42
1481990	0.635	12	0.45	2.99	12	408	0.21	0.42
1481991	0.390	<5	0.67	0.95	4	426	0.13	0.50

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
1481992	0.740	7	0.17	2.85	13	230	0.35	0.47
1481993	0.890	12	0.30	3.17	9	216	0.19	0.49
1481994	0.780	<5	0.19	3.07	7	206	0.17	0.56
1481995	0.765	5	0.10	3.00	5	177	0.14	0.55
1481996	0.665	5	0.11	2.42	7	210	0.16	0.49
1481997	0.455	6	0.21	2.41	8	230	0.27	0.63
1481998	0.725	8	0.32	2.01	8	277	0.18	0.60
1481999	0.460	7	0.12	2.84	11	149	0.18	0.29
1482000	0.560	6	0.14	3.12	10	187	0.21	0.31
1466523	0.450	6	0.06	2.00	9	162	0.15	0.48
1466551	0.460	<5	0.08	2.43	5	123	0.28	0.70
1466552	0.355	<5	0.12	1.99	16	120	3.58	0.46
1466553	0.530	22	0.28	2.66	155	209	5.65	0.53
1466554	0.355	18	0.73	1.70	84	266	2.62	0.41
1466555	0.545	19	0.54	2.63	52	530	4.45	0.72
1466556	0.560	14	0.46	2.29	30	193	1.77	0.56
1466557	0.520	9	0.37	2.21	9	220	3.21	0.51
1466558	0.400	11	0.50	1.63	10	139	2.50	0.58
1466559	0.590	8	0.29	1.95	6	171	7.80	0.67
1466560	0.365	11	0.55	1.84	20	206	3.09	0.80
1466561	0.515	13	0.48	1.98	27	219	2.71	0.70
1466562	0.310	13	0.41	1.08	18	105	1.36	0.35
1466563	0.380	7	0.28	1.86	15	87	2.16	1.10
1466564	0.385	7	0.33	1.69	25	121	1.07	0.60
1466565	0.290	10	0.59	2.15	22	114	2.22	0.59
1466566	0.520	14	0.26	2.33	21	220	2.05	0.76
1466567	0.445	7	0.08	2.25	15	127	0.19	0.30
1466568	0.600	6	0.13	2.99	11	169	0.17	0.68
1466569	0.520	9	0.13	2.51	48	178	0.18	0.39
1466570	0.490	5	0.11	2.32	7	196	0.15	0.41
1466571	0.455	6	0.08	2.41	13	182	0.22	0.48
1466572	0.470	8	0.07	2.43	12	197	0.21	0.47
1466573	0.525	11	0.09	2.51	37	180	0.29	0.38
1466574	0.580	9	0.13	2.33	29	118	0.28	0.39
1466575	0.705	11	0.26	2.65	40	132	0.37	0.36
1466813	0.325	13	0.24	1.62	8	143	2.69	0.54
*Rep 1466975		13						
*Rep 1481995		6						
*Rep 1466571		8						
*Std AMIS0474		152						

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
*Std OXN117	7600						
*Std OREAS251	488						
*Blk BLANK	<5						
*Blk BLANK	<5						
*Rep 1482000		0.13	3.14	10	190	0.19	0.31
*Rep 1466555		0.53	2.63	52	532	4.64	0.72
*Rep 1466562		0.37	1.06	17	102	1.34	0.35
*Std OREAS209		0.24	1.19	1050	66	0.05	1.50
*Std OREAS151B		0.49	2.47	32	62	0.37	1.37
*Std OREAS209		0.25	1.24	1110	70	0.07	1.54
*Blk BLANK		<0.01	<0.01	<1	<5	<0.02	<0.01
*Blk BLANK		<0.01	<0.01	<1	<5	<0.02	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd GE_IMS14B 0.01 ppm	Ce GE_IMS14B 0.05 ppm	Co GE_IMS14B 0.1 ppm	Cr GE_IMS14B 1 ppm	Cu GE_IMS14B 0.5 ppm	Fe GE_IMS14B 0.01 %	Ga GE_IMS14B 0.1 ppm	Hg GE_IMS14B 0.01 ppm
1466965	0.18	14.0	18.3	55	32.1	3.58	7.5	0.03
1466966	0.15	14.7	17.5	56	34.6	3.77	8.4	0.03
1466967	0.18	15.7	19.4	54	39.2	4.01	9.3	0.03
1466968	0.24	22.2	18.8	55	40.5	3.73	8.3	0.04
1466969	0.23	20.9	15.3	46	41.4	3.39	7.1	0.03
1466970	0.12	15.6	18.1	48	37.1	4.25	8.9	0.02
1466971	0.23	22.7	20.4	74	54.9	4.59	9.5	0.03
1466972	0.53	18.4	11.4	33	40.2	2.78	5.7	0.05
1466973	0.27	14.5	13.9	52	38.2	3.16	6.8	0.04
1466974	0.24	24.7	20.0	61	52.5	4.32	9.2	0.04
1466975	0.40	23.9	19.5	58	55.6	4.10	8.7	0.04
1466976	0.19	22.3	20.1	64	44.6	4.27	10.0	0.02
1466977	0.31	15.2	16.5	60	45.2	3.59	7.9	0.04
1466978	0.31	18.6	19.2	62	44.4	3.65	7.5	0.03
1466979	0.18	13.4	12.4	34	46.2	3.25	7.6	0.03
1466980	0.13	11.2	13.7	34	46.3	3.27	6.8	0.13
1466981	0.17	10.5	17.4	53	32.4	3.38	6.5	0.04
1480726	0.15	15.7	23.4	68	55.9	5.08	9.3	0.01
1480727	0.69	13.1	26.0	65	81.2	5.59	10.6	0.03
1480728	0.26	31.7	23.8	56	49.3	4.48	8.5	0.02
1480729	0.07	16.2	23.4	67	99.6	4.61	8.4	0.03
1480730	0.09	27.6	16.6	42	50.6	3.85	7.8	0.03
1480731	0.28	45.0	34.5	102	95.9	6.25	14.2	0.01
1480732	0.24	24.7	11.4	32	35.1	2.84	6.2	0.04
1480733	0.09	20.2	16.4	69	35.0	3.87	7.3	0.01
1480734	0.13	21.0	18.1	58	40.4	3.76	7.9	0.02
1480735	0.03	8.03	8.2	19	58.5	6.13	8.9	<0.01
1480736	0.13	14.4	24.1	55	52.0	4.38	7.8	0.04
1480737	0.12	17.7	17.3	51	52.4	3.82	7.7	0.04
1480738	0.31	15.4	9.0	37	26.2	2.59	6.2	0.02
1480739	0.26	17.1	10.6	45	35.7	3.37	7.3	0.04
1480740	0.40	26.3	20.6	93	55.6	4.57	10.4	0.05
1481984	0.10	15.2	19.9	53	59.3	4.41	7.9	0.05
1481985	0.17	19.4	19.9	58	62.7	4.34	8.3	0.03
1481986	0.44	18.8	17.6	52	41.1	3.79	8.4	0.02
1481987	0.70	22.6	15.6	90	56.4	3.85	9.1	0.05
1481988	0.51	21.1	17.4	58	53.6	3.91	8.7	0.08
1481989	0.27	21.0	13.2	61	45.8	3.61	8.0	0.06
1481990	0.67	23.7	16.5	65	62.8	4.27	8.4	0.05
1481991	1.45	16.1	9.3	21	54.6	1.51	3.5	0.05

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd GE_IMS14B 0.01 ppm	Ce GE_IMS14B 0.05 ppm	Co GE_IMS14B 0.1 ppm	Cr GE_IMS14B 1 ppm	Cu GE_IMS14B 0.5 ppm	Fe GE_IMS14B 0.01 %	Ga GE_IMS14B 0.1 ppm	Hg GE_IMS14B 0.01 ppm
1481992	0.28	14.8	23.4	67	51.0	4.47	8.2	0.04
1481993	0.08	18.5	18.9	62	53.7	4.44	7.8	0.02
1481994	0.14	19.0	17.4	53	46.5	4.02	8.5	0.02
1481995	0.08	24.6	16.2	70	43.4	3.84	7.9	0.03
1481996	0.12	27.9	15.3	51	36.5	3.48	6.5	0.04
1481997	0.13	31.0	14.4	45	42.6	3.45	6.8	0.04
1481998	0.38	29.5	10.8	32	41.7	2.99	6.3	0.05
1481999	0.18	29.5	15.2	42	39.5	3.69	7.1	0.02
1482000	0.18	32.5	17.4	46	50.1	3.90	7.5	0.02
1466523	0.12	63.6	8.8	29	37.0	3.43	6.3	0.03
1466551	0.12	9.73	16.6	26	70.1	3.05	6.4	<0.01
1466552	0.18	9.68	12.1	19	121	4.67	9.4	0.04
1466553	0.14	12.0	16.0	27	114	3.72	9.1	0.03
1466554	0.14	12.6	11.5	63	127	2.39	5.8	0.06
1466555	0.23	13.5	21.3	90	251	4.46	9.5	0.05
1466556	0.16	18.3	14.0	55	108	3.60	8.0	0.07
1466557	0.19	21.4	12.9	42	115	3.47	7.4	0.10
1466558	0.31	13.3	12.0	22	94.5	2.86	5.8	0.18
1466559	0.19	19.6	14.9	49	108	3.55	7.2	0.04
1466560	0.32	18.4	12.8	47	137	2.98	7.2	0.07
1466561	0.23	16.1	15.2	46	142	3.26	6.8	0.08
1466562	0.16	8.21	4.7	15	86.8	1.86	5.1	0.06
1466563	0.17	5.90	17.2	29	186	4.40	7.3	0.02
1466564	0.21	9.33	13.6	20	136	2.82	5.9	0.05
1466565	0.26	7.93	15.4	19	169	3.38	7.1	0.04
1466566	0.14	10.2	17.2	19	133	3.29	7.8	0.04
1466567	0.14	29.5	8.7	32	26.0	3.09	7.1	0.05
1466568	0.15	19.6	11.8	24	63.6	3.60	9.2	0.02
1466569	0.16	23.9	16.5	34	61.7	4.30	8.5	0.02
1466570	0.09	20.8	23.7	36	76.6	4.17	7.5	0.02
1466571	0.10	33.6	10.6	30	60.8	3.60	7.5	0.02
1466572	0.13	32.4	10.4	27	46.3	3.36	7.5	0.01
1466573	0.16	48.9	8.5	31	41.3	3.59	8.0	0.03
1466574	0.25	46.2	8.4	30	54.5	3.63	8.0	0.03
1466575	0.20	43.7	8.6	33	59.6	4.10	8.9	0.05
1466813	0.28	34.8	14.6	37	53.4	2.66	6.1	0.07

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	Cd	Ce	Co	Cr	Cu	Fe	Ga	Hg
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.01	0.05	0.1	1	0.5	0.01	0.1	0.01
Units	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
*Rep 1482000	0.17	32.0	17.6	46	50.2	3.89	7.5	0.02
*Rep 1466555	0.24	13.4	21.2	88	248	4.51	9.4	0.06
*Rep 1466562	0.14	7.95	4.6	15	84.8	1.84	5.1	0.06
*Std OREAS209	0.08	26.4	29.1	36	76.9	6.14	3.8	<0.01
*Std OREAS151B	0.59	15.5	11.6	24	1750	3.39	7.3	0.02
*Std OREAS209	0.08	28.0	30.4	39	78.4	6.41	4.2	<0.01
*Bik BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01
*Bik BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K GE_IMS14B 0.01 %	La GE_IMS14B 0.1 ppm	Mg GE_IMS14B 0.01 %	Mn GE_IMS14B 2 ppm	Mo GE_IMS14B 0.05 ppm	Na GE_IMS14B 0.01 %	Ni GE_IMS14B 0.5 ppm	P GE_IMS14B 50 ppm
1466965	0.41	6.8	1.88	550	0.67	0.03	30.9	730
1466966	0.50	7.1	1.91	578	0.73	0.03	32.7	700
1466967	0.50	8.0	1.81	666	0.99	0.06	36.2	710
1466968	0.44	10.9	1.74	669	0.87	0.04	36.1	720
1466969	0.41	10.5	1.61	663	0.75	0.03	28.2	630
1466970	0.72	7.9	2.16	728	0.71	0.04	32.1	560
1466971	0.62	11.7	2.61	861	0.82	0.04	47.1	790
1466972	0.14	9.5	1.11	608	0.87	0.03	26.0	770
1466973	0.29	7.3	1.57	522	0.77	0.03	33.1	730
1466974	0.66	12.1	2.19	792	0.80	0.03	36.2	650
1466975	0.51	11.6	2.00	830	0.72	0.04	35.6	670
1466976	0.63	10.6	2.23	712	0.90	0.04	43.3	790
1466977	0.54	7.5	1.85	533	0.75	0.03	37.3	800
1466978	0.37	9.2	1.80	651	1.05	0.02	38.8	760
1466979	0.21	6.7	1.31	328	0.77	0.02	19.6	540
1466980	0.22	5.7	1.29	346	1.31	0.02	18.4	620
1466981	0.17	5.2	1.47	419	0.98	0.02	27.3	700
1480726	0.49	5.8	2.28	751	0.87	0.02	38.9	500
1480727	0.75	6.3	3.15	1390	1.15	0.09	47.9	980
1480728	0.27	15.5	1.84	768	0.89	0.05	40.1	740
1480729	0.33	8.8	2.35	830	1.25	0.03	39.4	760
1480730	0.12	13.9	1.29	555	1.12	0.03	31.5	700
1480731	0.58	22.4	3.22	1180	1.35	0.08	89.5	1130
1480732	0.06	11.9	0.67	380	1.31	0.02	27.9	680
1480733	0.09	10.1	1.68	467	0.89	0.02	41.2	470
1480734	0.11	10.3	1.55	469	1.07	0.02	37.3	510
1480735	1.19	3.3	2.89	450	1.74	0.06	13.0	690
1480736	0.30	7.0	1.97	470	1.78	0.03	31.9	790
1480737	0.11	8.6	1.43	404	1.36	0.02	35.2	450
1480738	0.13	7.8	0.73	344	1.89	0.02	19.7	590
1480739	0.11	8.8	1.01	250	1.92	0.02	30.6	510
1480740	0.31	12.7	1.65	649	3.53	0.02	62.0	1010
1481984	0.24	7.4	1.93	366	1.10	0.02	32.1	560
1481985	0.17	9.2	1.50	603	1.83	0.02	39.3	730
1481986	0.29	9.6	1.38	644	2.66	0.02	37.3	710
1481987	0.27	12.0	1.59	548	4.16	0.03	49.8	950
1481988	0.18	10.7	1.17	552	4.70	0.03	43.7	800
1481989	0.13	10.6	1.24	361	3.04	0.02	41.5	610
1481990	0.19	11.7	1.29	478	2.74	0.02	52.2	690
1481991	0.09	8.2	0.35	322	1.46	0.03	19.5	900

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K GE_IMS14B 0.01 %	La GE_IMS14B 0.1 ppm	Mg GE_IMS14B 0.01 %	Mn GE_IMS14B 2 ppm	Mo GE_IMS14B 0.05 ppm	Na GE_IMS14B 0.01 %	Ni GE_IMS14B 0.5 ppm	P GE_IMS14B 50 ppm
1481992	0.22	7.1	1.93	884	2.01	0.02	38.7	550
1481993	0.25	9.2	1.83	402	0.99	0.02	36.0	540
1481994	0.18	9.8	1.58	466	1.27	0.02	30.9	530
1481995	0.18	12.5	1.83	428	0.82	0.03	39.9	510
1481996	0.07	13.5	1.13	410	1.15	0.02	34.2	570
1481997	0.06	15.3	0.98	481	1.57	0.02	31.8	840
1481998	0.07	16.8	0.68	291	1.33	0.02	27.1	570
1481999	0.07	11.4	0.86	393	1.18	0.02	36.0	350
1482000	0.08	10.9	1.00	360	0.99	0.02	45.7	330
1466523	0.18	36.5	0.66	529	0.69	0.02	19.5	880
1466551	0.13	4.6	1.31	213	0.68	0.07	18.6	1240
1466552	0.11	4.8	0.68	185	1.70	0.04	14.6	1890
1466553	0.21	5.6	0.96	483	8.70	0.06	19.8	1010
1466554	0.15	6.6	0.71	350	3.94	0.03	26.9	770
1466555	0.66	6.2	1.74	599	2.78	0.04	45.6	1160
1466556	0.21	8.6	1.04	456	2.05	0.03	34.3	790
1466557	0.16	10.5	0.84	456	3.24	0.03	25.0	720
1466558	0.06	6.4	0.56	787	1.93	0.03	15.1	1250
1466559	0.28	8.9	1.08	513	3.14	0.03	29.6	700
1466560	0.15	8.7	0.82	442	2.69	0.03	25.3	780
1466561	0.24	7.4	0.88	567	3.03	0.03	26.0	840
1466562	0.08	4.0	0.38	124	1.70	0.02	7.7	970
1466563	0.10	2.7	0.99	261	3.52	0.07	16.0	3800
1466564	0.11	4.4	0.71	258	2.78	0.05	15.3	1680
1466565	0.12	3.7	0.83	222	2.64	0.05	15.2	1480
1466566	0.21	4.7	0.97	364	2.50	0.05	15.6	1630
1466567	0.06	14.5	0.51	418	1.02	0.02	19.4	880
1466568	0.14	9.4	0.80	353	0.69	0.05	18.4	1520
1466569	0.31	11.0	0.96	478	1.76	0.03	19.8	870
1466570	0.28	11.2	0.87	237	1.72	0.03	20.3	780
1466571	0.15	21.1	0.68	590	1.45	0.03	17.3	930
1466572	0.17	17.1	0.73	486	0.85	0.03	20.3	910
1466573	0.16	27.2	0.62	571	1.08	0.02	18.3	600
1466574	0.14	26.9	0.67	483	1.09	0.02	20.5	750
1466575	0.09	26.7	0.62	491	1.55	0.02	18.8	800
1466813	0.16	19.1	0.74	602	1.82	0.03	19.9	770

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	K	La	Mg	Mn	Mo	Na	Ni	P
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.01	0.1	0.01	2	0.05	0.01	0.5	50
Units	%	ppm	%	ppm	ppm	%	ppm	ppm
*Rep 1482000	0.08	10.8	1.00	362	1.04	0.02	46.0	320
*Rep 1466555	0.66	6.3	1.73	600	2.65	0.04	45.7	1130
*Rep 1466562	0.08	3.9	0.38	123	1.64	0.03	7.6	970
*Std OREAS209	0.07	13.7	2.35	1240	1.84	0.19	110	1660
*Std OREAS151B	0.40	6.9	1.48	254	54.3	0.17	14.2	550
*Std OREAS209	0.07	13.8	2.44	1330	2.00	0.19	116	1720
*Bik BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50
*Bik BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
1466965	5.4	29.5	0.20	5.0	<0.3	24.1	1.4	0.13
1466966	5.6	36.1	0.20	5.7	0.3	24.8	1.7	0.14
1466967	5.8	36.8	0.23	7.4	0.4	27.5	1.6	0.13
1466968	7.5	34.9	0.34	5.9	0.4	29.5	1.7	0.13
1466969	6.5	32.5	0.43	5.0	0.3	29.1	1.5	0.12
1466970	7.1	46.1	0.34	5.3	0.4	19.7	2.5	0.19
1466971	10.9	42.2	0.35	6.4	0.4	25.3	2.7	0.14
1466972	6.5	17.0	0.47	4.0	0.3	37.8	0.9	0.09
1466973	5.3	28.5	0.32	4.4	0.3	34.8	1.1	0.11
1466974	9.8	43.3	0.46	6.9	0.5	20.2	2.9	0.16
1466975	9.1	38.1	0.47	6.3	0.4	26.0	2.0	0.14
1466976	7.9	43.6	0.24	7.0	0.5	22.9	2.7	0.15
1466977	5.4	34.1	0.23	5.1	0.3	32.0	1.5	0.14
1466978	6.6	29.0	0.25	5.7	0.3	25.2	1.9	0.13
1466979	5.6	19.3	0.21	3.9	0.4	22.6	1.0	0.15
1466980	99.4	18.5	0.29	3.6	0.4	22.1	0.8	0.14
1466981	10.2	18.8	0.28	3.8	0.3	23.4	0.7	0.13
1480726	7.5	33.2	0.26	5.0	0.4	20.4	1.6	0.19
1480727	8.9	48.2	0.20	6.7	<0.3	24.8	1.6	0.25
1480728	31.9	28.6	0.30	7.1	0.5	30.9	4.6	0.15
1480729	5.7	31.2	0.27	5.5	0.3	21.4	1.5	0.18
1480730	8.4	17.3	0.29	6.3	0.5	29.2	2.9	0.16
1480731	10.8	50.6	0.36	15.7	1.3	47.3	5.8	0.20
1480732	8.4	9.2	0.28	3.7	0.4	25.3	0.6	0.10
1480733	7.2	11.6	0.23	5.5	0.4	23.3	2.3	0.16
1480734	7.9	14.9	0.23	5.2	0.5	24.0	2.1	0.16
1480735	3.7	46.1	0.25	3.9	0.3	51.8	0.6	0.28
1480736	8.2	26.2	0.32	4.9	0.4	20.9	1.1	0.18
1480737	9.2	12.7	0.31	5.3	0.5	21.9	2.1	0.16
1480738	6.9	13.0	0.26	2.6	0.4	19.1	0.5	0.11
1480739	8.2	13.3	0.31	4.1	0.5	20.6	1.4	0.13
1480740	10.7	32.2	0.51	7.2	0.8	28.0	4.3	0.19
1481984	30.4	23.6	0.41	4.9	0.4	20.9	1.9	0.17
1481985	13.7	17.8	0.36	5.6	0.5	25.7	1.5	0.13
1481986	11.1	32.6	0.36	3.9	0.6	26.9	1.5	0.13
1481987	11.5	24.3	0.44	5.9	0.6	35.0	2.0	0.13
1481988	12.0	23.9	0.48	5.2	0.5	28.0	1.3	0.11
1481989	10.1	17.1	0.42	5.4	0.6	22.7	2.4	0.14
1481990	11.2	19.9	0.45	5.6	0.6	26.0	2.8	0.14
1481991	5.9	13.6	0.25	1.1	<0.3	28.5	<0.1	0.04

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
1481992	9.4	19.9	0.40	5.0	0.4	22.1	1.4	0.15
1481993	11.2	22.7	0.33	5.9	0.4	21.7	1.9	0.17
1481994	8.2	18.8	0.28	5.3	0.5	23.4	1.7	0.17
1481995	7.5	20.3	0.26	6.2	0.4	22.1	2.9	0.17
1481996	8.6	11.4	0.32	6.2	0.5	23.9	3.2	0.13
1481997	12.1	9.0	0.42	6.8	0.5	31.8	2.0	0.11
1481998	9.6	10.9	0.30	4.1	0.5	25.3	0.9	0.11
1481999	9.2	10.0	0.42	5.8	0.6	19.9	4.5	0.13
1482000	10.4	12.0	0.41	5.8	0.6	22.4	5.7	0.15
1466523	10.2	26.4	0.32	6.4	0.7	28.6	21.3	0.14
1466551	2.5	9.8	0.18	5.0	0.3	23.9	1.5	0.18
1466552	7.7	8.9	0.54	2.8	0.7	21.1	0.4	0.17
1466553	6.1	21.8	8.41	5.0	0.6	30.9	0.8	0.14
1466554	4.4	16.3	8.00	4.1	0.4	28.4	0.3	0.10
1466555	5.4	48.2	2.13	8.9	0.8	38.0	1.3	0.24
1466556	5.6	39.7	0.58	6.9	0.8	31.4	1.4	0.15
1466557	5.5	25.0	4.63	6.9	0.7	30.0	1.5	0.13
1466558	5.8	11.2	2.30	4.4	0.7	36.9	0.8	0.08
1466559	5.2	45.1	0.74	7.0	0.7	33.8	2.0	0.16
1466560	5.9	32.9	0.59	6.2	0.7	40.6	0.9	0.13
1466561	6.1	30.9	5.31	6.5	0.7	40.2	1.0	0.12
1466562	5.1	8.1	0.63	1.5	0.4	26.7	0.1	0.07
1466563	6.5	12.0	0.56	4.7	0.6	34.9	0.6	0.17
1466564	4.8	12.3	1.28	3.7	0.5	27.4	0.9	0.13
1466565	5.2	14.3	2.10	3.9	0.4	34.4	1.0	0.14
1466566	5.5	14.0	2.01	3.6	0.4	42.8	0.5	0.15
1466567	14.4	10.0	0.51	3.8	0.7	22.4	1.5	0.09
1466568	11.1	18.4	0.54	4.6	0.6	44.5	1.8	0.14
1466569	13.7	32.7	1.12	6.8	0.7	18.1	2.3	0.20
1466570	4.3	29.0	0.41	6.1	0.5	23.9	1.9	0.16
1466571	9.0	25.5	0.58	6.2	1.1	33.3	5.4	0.15
1466572	10.3	30.6	0.51	5.3	1.2	30.4	7.3	0.15
1466573	21.9	30.7	0.89	6.7	1.4	28.5	13.4	0.14
1466574	18.6	21.9	0.45	6.0	1.0	24.7	13.6	0.14
1466575	21.6	16.4	0.50	5.9	1.0	28.7	8.3	0.10
1466813	7.7	22.5	0.60	4.2	0.7	30.8	3.8	0.12

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
*Rep 1482000	10.3	11.9	0.39	5.7	0.6	22.7	5.6	0.15
*Rep 1466555	5.4	48.1	2.30	8.8	0.7	38.7	1.3	0.23
*Rep 1466562	5.0	8.2	0.66	1.5	0.4	26.2	<0.1	0.08
*Std OREAS209	3.4	3.6	1.15	3.2	0.8	57.6	1.6	0.14
*Std OREAS151B	42.9	18.4	0.50	8.3	1.0	34.4	2.4	0.08
*Std OREAS209	3.5	4.0	1.30	3.4	0.9	64.4	1.8	0.14
*Bik BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01
*Bik BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl	U	V	W	Y	Zn
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.02	0.05	1	0.1	0.05	1
	ppm	ppm	ppm	ppm	ppm	ppm
1466965	0.18	0.52	77	0.1	4.94	81
1466966	0.21	0.57	81	0.1	5.22	81
1466967	0.19	0.86	90	0.3	6.64	80
1466968	0.21	1.00	77	0.1	9.33	84
1466969	0.18	0.67	68	<0.1	8.87	99
1466970	0.26	0.48	90	0.2	5.49	117
1466971	0.26	0.83	91	0.1	10.2	128
1466972	0.10	0.80	56	0.1	8.96	86
1466973	0.16	0.70	65	0.1	6.27	80
1466974	0.25	0.73	88	<0.1	10.1	149
1466975	0.22	0.69	83	<0.1	10.3	131
1466976	0.30	1.01	92	0.2	7.87	94
1466977	0.20	0.63	76	0.2	5.55	87
1466978	0.18	1.14	77	0.7	8.00	93
1466979	0.14	0.55	66	0.2	3.85	64
1466980	0.24	0.48	62	0.1	3.57	109
1466981	0.22	0.46	60	<0.1	4.55	87
1480726	0.23	0.32	100	<0.1	4.35	110
1480727	0.28	0.48	142	<0.1	5.46	515
1480728	0.20	0.71	83	<0.1	11.3	111
1480729	0.26	0.84	92	<0.1	12.5	100
1480730	0.13	0.74	76	0.1	11.5	84
1480731	0.34	1.00	130	0.2	15.4	119
1480732	0.09	0.82	57	0.1	8.12	62
1480733	0.09	0.45	77	<0.1	5.73	75
1480734	0.12	0.53	75	0.1	5.81	79
1480735	0.65	0.21	83	<0.1	1.80	88
1480736	0.36	0.49	79	0.2	6.07	76
1480737	0.17	0.62	75	0.1	5.28	75
1480738	0.10	0.54	60	0.1	3.61	71
1480739	0.14	0.73	71	0.1	4.81	79
1480740	0.38	1.39	119	0.2	8.13	117
1481984	0.26	0.62	79	<0.1	4.83	89
1481985	0.16	0.72	83	0.1	5.88	91
1481986	0.20	0.68	87	0.2	5.35	124
1481987	0.23	1.28	103	0.1	8.60	131
1481988	0.24	1.39	93	0.1	9.08	101
1481989	0.21	0.93	87	0.1	7.17	100
1481990	0.21	1.12	91	0.2	7.68	116
1481991	0.09	1.15	27	0.2	6.91	56

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl	U	V	W	Y	Zn
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.02	0.05	1	0.1	0.05	1
	ppm	ppm	ppm	ppm	ppm	ppm
1481992	0.17	0.45	89	0.4	5.06	100
1481993	0.25	0.55	79	0.1	6.66	72
1481994	0.13	0.51	84	0.1	5.75	72
1481995	0.17	0.51	79	<0.1	6.40	76
1481996	0.10	1.00	66	0.1	9.61	67
1481997	0.10	1.30	73	0.1	11.8	65
1481998	0.08	1.35	57	0.1	11.6	62
1481999	0.09	0.77	71	0.2	6.03	67
1482000	0.11	0.77	73	0.1	6.12	76
1466523	0.32	3.60	58	0.2	14.2	77
1466551	0.11	0.44	76	1.0	2.85	53
1466552	0.13	0.29	119	3.1	2.24	42
1466553	0.24	0.45	80	3.3	4.98	72
1466554	0.18	0.67	48	3.7	7.86	47
1466555	0.43	0.69	116	11.8	7.84	98
1466556	0.30	1.87	87	2.1	9.29	85
1466557	0.27	3.37	74	1.5	11.1	68
1466558	0.25	8.63	63	7.7	9.29	70
1466559	0.32	1.97	83	9.8	9.35	80
1466560	0.25	1.43	72	3.8	10.9	80
1466561	0.30	0.75	73	6.9	7.77	76
1466562	0.09	0.48	32	5.4	2.53	35
1466563	0.12	0.18	127	7.0	2.70	52
1466564	0.11	0.32	69	38.0	2.95	54
1466565	0.11	0.32	84	2.4	3.07	48
1466566	0.13	0.36	81	1.3	4.04	64
1466567	0.18	1.75	58	0.2	9.76	54
1466568	0.18	1.09	79	5.2	7.94	66
1466569	0.31	1.56	92	0.2	8.48	76
1466570	0.27	2.50	92	0.2	12.0	64
1466571	0.31	9.38	71	0.6	15.1	73
1466572	0.39	4.11	68	0.7	11.9	73
1466573	0.39	9.10	62	0.3	19.3	83
1466574	0.30	4.99	63	1.6	18.3	111
1466575	0.27	7.61	67	0.5	22.3	109
1466813	0.27	2.69	59	5.0	9.54	64

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl GE_IMS14B 0.02 ppm	U GE_IMS14B 0.05 ppm	V GE_IMS14B 1 ppm	W GE_IMS14B 0.1 ppm	Y GE_IMS14B 0.05 ppm	Zn GE_IMS14B 1 ppm
*Rep 1482000	0.11	0.75	73	0.1	6.06	76
*Rep 1466555	0.44	0.68	114	11.1	7.77	97
*Rep 1466562	0.09	0.47	32	5.3	2.44	34
*Std OREAS209	0.03	0.41	36	0.3	12.3	77
*Std OREAS151B	0.12	0.55	131	0.5	9.96	240
*Std OREAS209	0.03	0.46	40	0.4	13.6	81
*Bik BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1
*Bik BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .