



Certificate of Analysis
Work Order : VC172169
[Report File No.: 0000023942]

Date: August 10, 2017

To: KENDRA JOHNSTON
INVOICE PAYMENT APPROVER
INDEPENDENCE GOLD CORP.
1020-625 HOWE STREET
VANCOUVER BC V6C 2T6

P.O. No.: BLVD-90403-05 / YK17_BLVD_DT1
Project No.: YK17_BLVD_DT1
Samples: 76
Received: Jul 13, 2017
Pages: Page 1 to 16
(Inclusive of Cover Sheet)

Methods Summary

<u>No. Of Samples</u>	<u>Method Code</u>	<u>Description</u>
76	G_LOG02	Pre-preparation processing, sorting, logging, boxing
76	G_WGH79	Weighing of samples and reporting of weights
76	GE_FAA313	@Au, FAS, AAS, 30g-5ml(Final Mode)
76	GE_IMS14B	Aqua Regia digestion/ICP-MS package

Storage: Pulp & Reject

REJECT STORAGE : DISPOSE AFTER 30 DAYS
PULP STORAGE : DISPOSE AFTER 90 DAYS

Certified By : _____

John Chiang
QC Chemist

SGS Minerals Services Geochemistry Vancouver conforms to the requirements of ISO/IEC 17025 for specific tests as listed on their scope of accreditation which can be found at <http://www.scc.ca/en/search/palcan/sgs>

Report Footer:

L.N.R. = Listed not received
n.a. = Not applicable

I.S. = Insufficient Sample
-- = No result

*INF = Composition of this sample makes detection impossible by this method
M after a result denotes ppb to ppm conversion, % denotes ppm to % conversion

Methods marked with an asterisk (e.g. *NAA08V) were subcontracted

Elements marked with the @ symbol (e.g. @Cu) denote assays performed using accredited test methods

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
1466814	0.255	<5	0.31	1.42	4	83	1.79	0.30
1466815	0.325	<5	0.22	1.69	3	137	1.82	0.44
1466816	0.490	7	0.17	1.85	9	122	1.68	0.39
1466817	0.350	<5	0.19	1.67	8	128	1.74	0.37
1466818	0.295	<5	0.19	1.93	4	228	1.17	0.69
1466819	0.295	<5	0.19	1.58	5	140	1.01	0.45
1466820	0.255	<5	0.06	0.43	6	33	0.62	0.07
1466821	0.290	6	0.39	1.00	5	85	2.98	0.30
1466822	0.290	6	0.38	0.78	5	74	1.19	0.47
1466823	0.270	7	0.31	1.17	9	112	1.42	0.40
1466826	0.400	<5	0.27	1.70	9	110	1.69	0.34
1466827	0.385	<5	0.12	2.07	4	297	0.58	0.42
1466828	0.190	<5	0.52	1.75	4	491	3.27	0.99
1466829	0.440	8	0.21	1.73	4	110	10.7	0.49
1466830	0.440	9	0.28	2.17	9	119	6.28	0.51
1466831	0.490	7	0.12	2.30	7	181	1.40	0.46
1466832	0.390	<5	0.16	0.59	2	52	1.81	0.09
1466833	0.415	7	0.12	2.55	18	114	1.39	0.17
1466834	0.285	8	0.19	1.41	3	138	0.85	0.66
1466835	0.260	9	0.24	1.21	5	102	1.38	0.35
1466836	0.345	7	0.31	1.38	9	100	1.83	0.44
1466837	0.310	7	0.28	1.32	13	72	1.51	0.56
1466838	0.510	11	1.28	2.76	20	180	7.87	1.01
1466839	0.350	9	0.71	1.91	11	214	2.05	0.53
1466840	0.280	<5	0.14	1.45	10	108	0.45	0.54
1466841	0.415	8	0.15	2.69	27	182	2.48	0.37
1466842	0.380	<5	0.21	0.25	<1	24	0.09	0.06
1466501	0.655	<5	0.16	1.64	7	97	0.13	0.35
1466502	0.535	5	0.14	1.50	7	90	0.13	0.35
1466503	0.425	5	0.17	2.30	8	147	0.13	0.30
1466504	0.345	<5	0.09	1.54	4	86	0.11	0.36
1466505	0.375	9	0.09	1.94	4	109	0.09	0.42
1466506	0.415	6	0.12	1.88	9	110	0.10	0.28
1466507	0.620	6	0.16	2.73	10	212	0.08	1.15
1466508	0.310	7	0.18	2.76	11	195	0.08	1.72
1466509	0.460	<5	0.15	3.30	5	187	0.11	0.79
1466510	0.530	5	0.22	3.38	6	229	0.12	0.77
1466511	0.280	6	0.19	2.66	4	226	0.09	1.22
1466512	0.535	7	0.15	2.91	5	223	0.14	0.93
1466513	0.310	<5	0.24	2.50	5	297	0.13	1.67

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	WtKg G_WGH79 0.01 kg	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
1466514	0.565	7	0.18	2.53	5	211	0.14	0.92
1466515	0.670	5	0.18	2.47	5	231	0.13	1.16
1466516	0.635	<5	0.17	2.32	7	205	0.16	0.95
1466517	0.520	<5	0.24	2.23	10	276	0.24	0.87
1466518	0.380	<5	0.16	1.55	11	296	0.13	1.19
1466519	0.585	<5	0.12	2.57	9	249	0.19	0.72
1466520	0.635	23	0.24	2.50	10	331	0.24	0.67
1466521	0.500	<5	0.16	2.06	6	249	0.16	1.23
1466522	0.570	<5	0.17	2.17	5	297	0.11	1.44
1466542	0.460	<5	0.08	2.52	4	149	0.09	0.78
1466543	0.425	6	0.12	2.75	5	204	0.11	0.56
1466544	0.370	6	0.08	2.17	4	123	0.10	0.47
1466545	0.405	5	0.19	1.77	6	130	0.11	0.53
1466546	0.340	10	0.11	1.51	4	93	0.11	0.38
1466547	0.580	<5	0.08	2.18	8	114	0.10	0.50
1466548	0.370	<5	0.09	1.68	7	101	0.10	0.42
1466549	0.345	6	0.14	1.33	4	83	0.11	0.33
1466550	0.345	<5	0.12	1.27	4	80	0.10	0.33
1467063	0.475	7	0.21	1.53	3	117	0.08	0.36
1467064	0.630	<5	0.11	2.55	6	185	0.13	0.45
1467065	0.505	<5	0.13	2.94	9	251	0.20	0.42
1467066	0.505	<5	0.13	2.66	7	177	0.16	0.40
1467067	0.580	14	0.33	2.96	11	265	0.28	0.42
1467068	0.660	5	0.12	3.24	5	286	0.12	0.58
1467069	0.625	6	0.14	2.96	6	226	0.18	0.60
1467070	0.595	9	0.24	5.66	5	521	0.16	1.30
1467071	0.615	16	0.08	3.18	5	260	0.10	0.58
1467072	0.495	<5	0.08	3.16	5	207	0.16	0.44
1467073	0.495	8	0.10	3.35	9	258	0.25	0.47
1467074	0.480	6	0.13	3.55	7	177	0.20	0.53
1467075	0.520	<5	0.11	3.70	6	188	0.22	0.52
1467101	0.370	<5	0.37	0.77	4	83	0.09	0.14
1467102	0.505	13	0.89	2.43	13	448	0.22	0.33
1467103	0.615	<5	0.50	1.13	6	159	0.14	0.33
1481101	0.720	5	0.22	3.00	7	502	0.23	0.65
1481102	0.575	<5	0.16	2.29	5	184	0.12	0.53
*Rep 1466831		<5						
*Rep 1466518		<5						
*Rep 1466543		6						
*Std AMIS0474		157						

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	@Au GE_FAA313 5 ppb	Ag GE_IMS14B 0.01 ppm	Al GE_IMS14B 0.01 %	As GE_IMS14B 1 ppm	Ba GE_IMS14B 5 ppm	Bi GE_IMS14B 0.02 ppm	Ca GE_IMS14B 0.01 %
*Std OXN117	7630						
*Std OREAS251	480						
*Blk BLANK	<5						
*Blk BLANK	<5						
*Rep 1466815		0.21	1.71	3	131	1.75	0.44
*Rep 1466837		0.26	1.36	13	71	1.77	0.60
*Rep 1467067		0.33	2.90	11	262	0.26	0.41
*Std OREAS209		0.24	1.23	1080	66	0.06	1.52
*Std OREAS151B		0.49	2.46	32	60	0.37	1.36
*Std OREAS209		0.24	1.18	1060	67	0.06	1.49
*Blk BLANK		<0.01	<0.01	<1	<5	<0.02	<0.01
*Blk BLANK		<0.01	<0.01	<1	<5	<0.02	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd	Ce	Co	Cr	Cu	Fe	Ga	Hg
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.01	0.05	0.1	1	0.5	0.01	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
1466814	0.12	14.9	5.8	48	40.7	1.76	6.0	0.07
1466815	0.16	17.3	10.2	60	64.9	2.31	5.9	0.05
1466816	0.13	14.8	16.6	72	73.3	2.74	5.7	0.05
1466817	0.15	17.1	14.5	66	53.7	2.75	6.4	0.04
1466818	0.19	26.2	13.0	83	49.6	2.76	7.4	0.05
1466819	0.19	30.2	18.2	47	46.9	2.50	5.8	0.16
1466820	0.06	5.28	1.9	10	12.5	1.22	3.9	0.04
1466821	0.21	11.1	6.4	16	43.1	1.66	4.0	0.11
1466822	0.14	5.68	3.7	11	74.4	1.34	3.1	0.08
1466823	0.15	10.1	5.3	16	69.3	1.98	4.5	0.11
1466826	0.12	16.9	16.9	36	71.1	2.73	7.0	0.06
1466827	0.11	14.9	13.6	72	53.5	3.16	8.8	0.03
1466828	0.37	113	10.1	40	174	2.57	6.6	0.11
1466829	0.09	10.7	12.7	71	120	2.68	6.6	0.02
1466830	0.19	12.0	17.3	111	202	2.89	5.8	0.04
1466831	0.10	24.5	13.4	68	105	3.06	6.7	0.02
1466832	0.12	6.08	2.4	12	19.7	0.99	3.3	0.02
1466833	0.22	14.4	8.3	34	20.8	4.04	10.3	0.05
1466834	0.18	42.7	10.2	27	50.0	2.00	4.5	0.11
1466835	0.14	14.9	4.9	20	59.0	1.71	5.3	0.06
1466836	0.21	7.58	8.0	15	110	2.14	5.8	0.04
1466837	0.10	5.95	8.5	17	88.1	2.27	5.2	0.03
1466838	1.00	9.48	30.6	30	1190	4.57	6.9	0.41
1466839	0.42	11.8	11.8	43	153	3.03	7.6	0.12
1466840	0.31	10.5	6.4	20	31.2	2.78	6.5	0.06
1466841	0.21	15.2	18.9	30	109	4.08	8.6	0.03
1466842	0.03	4.79	1.2	4	8.4	0.48	1.5	0.03
1466501	0.13	15.1	9.2	29	17.1	2.62	5.8	0.03
1466502	0.14	12.3	8.5	28	21.8	2.23	5.6	0.04
1466503	0.17	12.6	11.6	37	25.5	3.16	7.1	0.04
1466504	0.11	9.30	6.1	32	17.2	2.11	6.0	0.03
1466505	0.11	8.71	8.1	40	19.1	2.39	6.5	0.04
1466506	0.13	11.4	7.5	33	17.5	2.66	6.4	0.05
1466507	0.22	15.7	15.2	44	34.4	3.45	7.4	0.03
1466508	0.21	14.5	15.6	47	34.0	3.30	7.5	0.04
1466509	0.12	14.1	16.6	50	30.9	4.06	8.9	0.03
1466510	0.16	18.8	17.7	51	42.3	4.19	9.0	0.02
1466511	0.32	21.5	13.4	43	33.3	3.27	7.4	0.05
1466512	0.21	21.4	14.6	50	40.6	3.64	8.0	0.03
1466513	0.42	24.9	13.0	43	49.8	3.13	6.8	0.04

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Cd GE_IMS14B 0.01 ppm	Ce GE_IMS14B 0.05 ppm	Co GE_IMS14B 0.1 ppm	Cr GE_IMS14B 1 ppm	Cu GE_IMS14B 0.5 ppm	Fe GE_IMS14B 0.01 %	Ga GE_IMS14B 0.1 ppm	Hg GE_IMS14B 0.01 ppm
1466514	0.24	20.1	13.5	46	33.7	3.33	7.1	0.03
1466515	0.24	23.3	14.5	41	41.9	3.38	6.9	0.04
1466516	0.22	16.5	13.7	40	30.0	3.38	6.9	0.03
1466517	0.24	31.2	12.6	36	29.1	3.17	7.0	0.06
1466518	0.55	21.0	9.5	29	34.5	2.49	5.2	0.06
1466519	0.21	27.2	13.3	45	33.3	3.71	8.1	0.02
1466520	0.20	35.3	14.9	44	35.5	3.49	7.0	0.08
1466521	0.23	24.0	12.7	36	29.5	3.00	6.1	0.07
1466522	0.27	18.7	12.5	38	36.2	2.98	6.3	0.03
1466542	0.09	10.3	15.8	46	25.6	3.20	7.3	0.02
1466543	0.10	15.7	14.5	45	40.4	3.55	7.9	0.03
1466544	0.07	10.5	13.7	39	24.2	2.99	6.6	0.03
1466545	0.14	11.3	16.5	31	23.0	2.94	5.8	0.05
1466546	0.11	10.8	7.5	26	16.6	2.09	5.6	0.04
1466547	0.10	12.5	17.8	37	19.4	3.30	6.8	0.03
1466548	0.17	13.3	12.4	28	17.7	2.73	5.3	0.03
1466549	0.12	11.4	5.2	23	15.7	1.78	5.5	0.04
1466550	0.13	11.4	4.9	22	15.5	1.71	5.2	0.04
1467063	0.09	9.98	9.4	38	21.8	2.12	4.7	0.04
1467064	0.09	22.7	13.0	46	35.4	3.34	6.9	0.04
1467065	0.20	26.1	15.4	41	38.3	3.94	7.8	0.02
1467066	0.14	21.7	14.3	43	33.8	3.67	7.9	0.03
1467067	0.21	50.9	24.0	60	62.0	4.94	8.2	0.04
1467068	0.04	21.0	20.3	72	69.0	4.66	8.9	0.03
1467069	0.12	30.6	21.1	60	50.9	4.42	9.0	0.03
1467070	0.46	25.6	38.2	72	83.6	7.43	15.2	<0.01
1467071	0.05	20.1	20.1	68	39.5	4.31	8.3	0.02
1467072	0.12	28.6	22.8	50	58.5	4.51	8.4	0.01
1467073	0.08	25.8	18.4	57	45.0	4.31	8.7	0.02
1467074	0.09	25.3	22.7	53	89.3	4.88	9.5	0.02
1467075	0.12	28.2	25.3	55	101	5.13	10.0	0.02
1467101	0.36	7.02	4.9	12	17.0	1.28	3.6	0.03
1467102	1.22	27.7	13.6	51	104	4.16	6.8	0.23
1467103	0.70	12.6	9.2	30	34.9	2.03	4.6	0.05
1481101	0.22	30.8	17.1	69	56.2	4.55	8.4	0.03
1481102	0.09	20.1	11.8	43	33.0	2.85	6.1	0.04

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	Cd	Ce	Co	Cr	Cu	Fe	Ga	Hg
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.01	0.05	0.1	1	0.5	0.01	0.1	0.01
Units	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm
*Rep 1466815	0.17	16.7	10.3	61	64.4	2.30	5.8	0.05
*Rep 1466837	0.10	6.67	8.6	17	89.3	2.31	5.3	0.02
*Rep 1467067	0.22	49.4	23.5	58	60.9	4.83	8.1	0.04
*Std OREAS209	0.07	26.4	29.1	37	80.7	6.27	4.0	<0.01
*Std OREAS151B	0.63	15.4	11.3	24	1740	3.36	7.4	0.02
*Std OREAS209	0.07	27.4	29.5	36	79.0	6.21	3.9	<0.01
*Bik BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01
*Bik BLANK	<0.01	<0.05	<0.1	<1	<0.5	<0.01	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K GE_IMS14B 0.01 %	La GE_IMS14B 0.1 ppm	Mg GE_IMS14B 0.01 %	Mn GE_IMS14B 2 ppm	Mo GE_IMS14B 0.05 ppm	Na GE_IMS14B 0.01 %	Ni GE_IMS14B 0.5 ppm	P GE_IMS14B 50 ppm
1466814	0.09	7.9	0.63	134	0.57	0.02	21.0	620
1466815	0.13	9.0	0.90	207	0.63	0.03	31.9	630
1466816	0.13	7.9	0.98	554	0.71	0.03	31.3	590
1466817	0.12	9.0	0.88	487	0.91	0.03	27.6	560
1466818	0.18	14.2	1.25	298	0.71	0.03	45.3	570
1466819	0.12	16.2	0.78	391	0.81	0.02	40.1	830
1466820	0.03	2.7	0.07	54	0.95	0.02	4.6	340
1466821	0.06	6.2	0.31	104	0.74	0.02	9.4	800
1466822	0.06	2.9	0.24	59	2.50	0.03	6.0	800
1466823	0.07	5.1	0.38	118	2.75	0.03	8.4	860
1466826	0.14	9.0	0.64	533	5.95	0.03	18.4	560
1466827	0.31	7.5	1.25	406	2.28	0.03	48.9	500
1466828	0.27	91.8	0.90	333	3.27	0.03	41.4	780
1466829	0.13	5.4	0.99	229	2.95	0.04	32.7	330
1466830	0.14	6.2	1.27	256	2.38	0.04	42.3	410
1466831	0.19	12.8	1.12	320	1.59	0.03	33.9	530
1466832	0.05	3.3	0.19	69	0.79	0.02	6.5	190
1466833	0.05	7.2	0.44	263	2.52	0.02	21.5	360
1466834	0.14	27.7	0.44	242	1.31	0.02	27.0	1010
1466835	0.08	8.2	0.39	97	1.45	0.02	9.9	620
1466836	0.07	3.8	0.56	139	4.52	0.04	10.0	570
1466837	0.07	3.0	0.70	139	3.67	0.05	10.7	880
1466838	0.24	4.7	1.27	392	5.95	0.07	24.1	2610
1466839	0.09	6.1	0.87	260	5.73	0.03	21.6	650
1466840	0.07	5.1	0.32	329	1.50	0.02	11.1	710
1466841	0.19	7.7	0.91	419	2.25	0.03	18.6	670
1466842	0.03	2.8	0.06	25	0.27	0.03	2.0	130
1466501	0.07	7.8	0.76	292	1.58	0.02	19.6	640
1466502	0.06	6.5	0.66	180	1.27	0.02	17.2	650
1466503	0.12	6.3	0.88	337	1.66	0.02	18.3	540
1466504	0.09	4.8	0.75	148	0.71	0.02	16.4	540
1466505	0.18	4.4	1.09	196	0.57	0.03	20.2	540
1466506	0.11	5.8	0.84	192	1.25	0.02	18.5	580
1466507	0.49	8.1	1.67	613	0.72	0.04	25.7	650
1466508	0.37	7.4	1.50	670	0.86	0.04	26.3	780
1466509	0.43	7.3	1.75	579	0.75	0.04	27.5	400
1466510	0.49	9.9	1.83	713	0.81	0.03	29.7	500
1466511	0.37	10.6	1.45	528	0.82	0.05	26.2	600
1466512	0.39	11.3	1.64	528	0.74	0.03	30.1	590
1466513	0.20	13.3	1.21	552	0.96	0.04	32.6	680

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	K	La	Mg	Mn	Mo	Na	Ni	P
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.01	0.1	0.01	2	0.05	0.01	0.5	50
	%	ppm	%	ppm	ppm	%	ppm	ppm
1466514	0.15	10.2	1.34	478	1.06	0.02	30.0	590
1466515	0.25	12.0	1.36	533	1.45	0.03	29.0	780
1466516	0.15	8.1	1.18	404	1.32	0.03	26.7	480
1466517	0.13	14.8	0.75	458	1.96	0.02	25.8	390
1466518	0.14	10.7	0.64	377	1.25	0.02	26.0	590
1466519	0.18	11.1	0.96	414	1.55	0.02	34.0	430
1466520	0.11	16.7	0.95	495	1.59	0.02	31.9	390
1466521	0.14	11.6	0.97	455	1.27	0.03	24.5	540
1466522	0.20	8.6	1.13	605	1.15	0.03	27.3	640
1466542	0.20	4.9	1.43	459	0.50	0.04	23.8	530
1466543	0.20	7.5	1.45	380	0.63	0.03	23.2	580
1466544	0.13	5.2	1.27	411	0.64	0.03	18.8	580
1466545	0.07	5.4	0.86	771	0.99	0.02	17.9	810
1466546	0.05	5.3	0.67	208	0.52	0.02	13.9	640
1466547	0.09	5.8	1.10	669	0.71	0.03	21.5	650
1466548	0.06	6.4	0.71	467	0.83	0.02	17.0	700
1466549	0.06	5.7	0.54	129	0.84	0.02	13.2	610
1466550	0.05	5.6	0.51	121	0.81	0.02	12.4	600
1467063	0.11	4.9	0.93	295	0.67	0.03	19.4	590
1467064	0.06	10.7	1.06	305	0.88	0.02	30.6	480
1467065	0.10	10.6	0.97	440	1.28	0.02	38.2	560
1467066	0.08	10.0	1.05	407	1.10	0.02	28.1	410
1467067	0.09	21.3	1.10	874	2.27	0.02	59.1	780
1467068	0.45	10.0	2.26	604	0.69	0.02	41.6	450
1467069	0.17	13.7	1.75	817	1.38	0.02	40.7	750
1467070	1.33	15.6	4.63	1990	1.92	0.12	45.2	720
1467071	0.37	9.7	2.09	569	0.62	0.03	39.8	580
1467072	0.30	10.6	1.94	643	0.88	0.02	34.3	480
1467073	0.09	11.3	1.48	536	1.02	0.02	37.4	500
1467074	0.14	10.7	2.07	675	1.54	0.03	38.7	600
1467075	0.18	12.1	2.28	772	1.68	0.03	40.4	670
1467101	0.04	3.4	0.20	153	1.15	0.03	10.6	360
1467102	0.14	13.1	0.87	321	4.41	0.02	46.4	1090
1467103	0.08	6.0	0.56	278	2.18	0.02	25.0	700
1481101	0.22	14.5	1.56	514	1.84	0.03	56.0	790
1481102	0.08	10.2	0.98	277	0.85	0.03	27.6	430

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	K	La	Mg	Mn	Mo	Na	Ni	P
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.01	0.1	0.01	2	0.05	0.01	0.5	50
Units	%	ppm	%	ppm	ppm	%	ppm	ppm
*Rep 1466815	0.13	8.6	0.91	208	0.57	0.03	31.3	630
*Rep 1466837	0.07	3.3	0.72	147	4.08	0.06	10.6	880
*Rep 1467067	0.09	20.0	1.07	857	2.24	0.02	57.8	740
*Std OREAS209	0.07	13.6	2.37	1270	1.91	0.19	111	1680
*Std OREAS151B	0.40	6.8	1.46	253	56.4	0.17	14.0	540
*Std OREAS209	0.07	13.6	2.31	1230	1.86	0.18	112	1690
*Bik BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50
*Bik BLANK	<0.01	<0.1	<0.01	<2	<0.05	<0.01	<0.5	<50

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
1466814	7.2	22.9	0.21	2.6	0.7	16.8	0.6	0.07
1466815	6.1	24.1	0.22	4.3	0.7	22.1	1.2	0.10
1466816	5.1	19.4	0.22	4.7	0.5	19.2	1.0	0.10
1466817	7.4	23.3	0.51	3.8	0.7	19.6	1.2	0.12
1466818	8.8	35.1	0.26	5.1	0.7	37.2	2.0	0.16
1466819	9.8	25.4	0.32	3.6	0.5	30.0	1.4	0.11
1466820	9.3	4.5	0.28	0.8	0.4	6.6	0.1	0.06
1466821	11.6	7.7	0.32	2.0	0.3	21.5	0.3	0.07
1466822	4.8	6.1	0.47	1.5	<0.3	29.9	<0.1	0.06
1466823	3.9	8.9	0.40	2.1	0.4	28.9	0.2	0.08
1466826	7.3	19.3	0.31	3.8	0.6	19.4	1.2	0.13
1466827	5.7	32.5	0.20	5.8	0.7	20.4	1.6	0.17
1466828	10.1	39.7	0.38	6.8	0.7	50.4	4.7	0.13
1466829	4.4	21.4	0.22	4.6	0.6	19.2	1.4	0.15
1466830	3.5	20.5	0.34	5.1	0.5	20.3	1.3	0.15
1466831	6.3	28.2	0.26	5.3	0.6	23.6	3.1	0.17
1466832	4.3	9.3	0.13	1.3	0.3	6.8	0.6	0.07
1466833	18.5	12.3	0.78	3.3	0.8	12.3	2.8	0.15
1466834	4.2	18.1	0.23	3.4	0.4	41.3	1.8	0.08
1466835	5.0	11.6	0.29	2.9	0.4	21.2	0.5	0.10
1466836	5.7	8.4	0.50	2.1	0.4	30.9	0.2	0.11
1466837	5.5	6.8	1.03	3.1	0.4	27.2	0.3	0.11
1466838	9.9	20.0	5.54	4.4	0.9	58.1	0.8	0.17
1466839	7.4	9.5	0.89	4.5	0.7	33.4	0.6	0.14
1466840	6.5	11.7	0.64	1.9	0.6	29.4	0.3	0.10
1466841	5.7	19.1	1.03	5.1	0.6	26.1	1.6	0.18
1466842	2.2	4.3	0.08	0.6	<0.3	5.7	0.3	0.04
1466501	6.8	8.8	0.30	3.1	0.4	19.3	1.3	0.12
1466502	6.1	7.8	0.22	2.7	0.4	18.5	0.7	0.10
1466503	7.3	10.4	0.24	4.8	0.4	17.7	0.8	0.11
1466504	5.4	9.1	0.18	2.4	0.3	15.6	0.4	0.10
1466505	4.4	14.0	0.18	2.9	0.3	16.1	0.5	0.13
1466506	5.8	10.6	0.24	3.7	0.3	14.4	0.5	0.10
1466507	6.1	35.6	0.27	4.8	<0.3	27.2	1.4	0.13
1466508	5.8	32.1	0.31	5.6	0.3	37.4	1.0	0.11
1466509	9.2	34.4	0.20	5.7	0.4	21.8	2.0	0.16
1466510	9.6	38.8	0.22	6.6	0.5	21.9	2.3	0.16
1466511	8.6	31.2	0.27	5.0	0.3	32.8	2.0	0.13
1466512	9.3	27.6	0.25	5.5	0.4	24.4	2.7	0.14
1466513	11.1	24.0	0.31	4.8	0.4	40.6	1.7	0.10

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
1466514	11.1	17.4	0.25	5.0	0.4	25.9	2.3	0.11
1466515	9.5	24.0	0.27	5.4	0.4	28.6	2.8	0.11
1466516	11.0	17.1	0.24	4.8	0.5	25.8	2.7	0.12
1466517	15.4	15.4	0.36	4.8	0.6	26.0	4.2	0.10
1466518	7.8	13.4	0.33	3.3	0.4	26.7	1.8	0.08
1466519	11.8	23.6	0.32	4.9	0.6	22.0	3.7	0.13
1466520	15.9	12.2	0.32	5.9	0.6	23.9	5.8	0.11
1466521	10.2	16.4	0.29	5.0	0.5	31.2	2.8	0.10
1466522	7.6	20.1	0.27	4.5	0.4	34.7	2.1	0.11
1466542	4.5	17.4	0.23	4.6	0.3	25.0	1.0	0.15
1466543	5.3	19.4	0.23	5.0	0.4	20.2	1.4	0.16
1466544	4.7	13.0	0.21	3.8	0.8	16.5	0.9	0.14
1466545	5.4	10.8	0.27	3.3	0.3	22.3	0.6	0.09
1466546	5.6	9.1	0.22	2.7	0.4	17.9	0.4	0.09
1466547	5.6	11.9	0.23	4.1	0.4	19.7	1.0	0.13
1466548	5.6	8.7	0.24	3.2	0.4	19.4	0.7	0.10
1466549	6.0	8.4	0.22	2.2	0.4	18.3	0.3	0.09
1466550	5.6	8.1	0.22	2.2	0.4	17.7	0.3	0.08
1467063	4.2	11.4	0.20	2.5	<0.3	16.9	0.4	0.08
1467064	7.4	10.5	0.42	5.0	0.5	22.3	2.0	0.14
1467065	9.5	12.5	0.38	5.6	0.6	22.6	2.6	0.15
1467066	8.4	13.2	0.31	5.5	0.5	22.0	2.2	0.16
1467067	13.5	13.4	0.40	6.3	0.7	26.1	4.7	0.11
1467068	6.3	39.1	0.28	7.7	0.5	19.0	2.5	0.18
1467069	10.2	21.2	0.31	7.7	0.5	26.0	2.5	0.13
1467070	18.1	73.6	0.20	15.6	0.6	58.0	5.2	0.18
1467071	5.6	32.7	0.26	6.2	0.4	21.4	1.9	0.17
1467072	12.2	26.0	0.23	6.3	0.5	19.0	3.7	0.15
1467073	7.9	12.7	0.28	7.7	0.6	22.0	3.4	0.16
1467074	9.0	16.2	0.27	6.6	0.5	19.3	3.2	0.16
1467075	8.8	18.4	0.27	6.9	0.5	19.3	3.5	0.16
1467101	4.3	6.5	0.20	1.3	<0.3	9.9	0.2	0.06
1467102	9.2	14.2	0.58	4.1	0.5	32.7	1.0	0.10
1467103	5.4	10.7	0.31	1.5	0.3	19.6	0.1	0.07
1481101	13.7	25.2	0.31	7.7	0.6	26.5	4.7	0.13
1481102	6.2	10.6	0.25	4.3	0.4	17.6	1.6	0.12

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element	Pb	Rb	Sb	Sc	Sn	Sr	Th	Ti
Method	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
Det.Lim.	0.2	0.2	0.05	0.1	0.3	0.5	0.1	0.01
Units	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
*Rep 1466815	5.9	24.0	0.21	4.3	0.7	21.7	1.1	0.10
*Rep 1466837	5.5	7.0	0.97	3.4	0.4	28.1	0.3	0.13
*Rep 1467067	13.3	13.2	0.39	6.0	0.6	25.8	4.6	0.11
*Std OREAS209	4.0	3.8	1.22	3.4	0.9	60.8	1.7	0.15
*Std OREAS151B	42.8	18.7	0.52	8.4	1.0	35.3	2.3	0.08
*Std OREAS209	3.4	3.8	1.19	3.3	0.9	59.3	1.7	0.14
*Bik BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01
*Bik BLANK	<0.2	<0.2	<0.05	<0.1	<0.3	<0.5	<0.1	<0.01

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl	U	V	W	Y	Zn
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.02	0.05	1	0.1	0.05	1
	ppm	ppm	ppm	ppm	ppm	ppm
1466814	0.30	1.01	34	0.3	3.66	48
1466815	0.29	1.06	49	0.4	5.26	55
1466816	0.24	1.17	65	0.8	4.47	52
1466817	0.23	1.24	67	0.4	4.42	55
1466818	0.29	1.65	64	0.2	6.54	69
1466819	0.24	1.77	45	0.3	7.18	55
1466820	0.11	0.38	36	0.2	0.89	17
1466821	0.13	1.51	25	0.5	4.40	37
1466822	0.08	0.29	20	1.5	1.96	23
1466823	0.13	0.48	28	3.7	3.50	36
1466826	0.18	0.61	69	28.9	4.25	60
1466827	0.28	0.78	76	0.9	3.91	75
1466828	0.39	14.6	55	0.7	62.1	59
1466829	0.20	0.52	74	2.6	3.71	48
1466830	0.23	0.53	67	8.6	4.71	48
1466831	0.27	0.94	73	0.7	7.08	58
1466832	0.08	0.31	27	0.3	1.37	19
1466833	0.15	0.57	92	0.9	2.57	57
1466834	0.18	1.23	29	3.5	9.34	44
1466835	0.13	0.62	30	3.8	5.51	36
1466836	0.11	0.33	51	4.2	2.63	42
1466837	0.10	0.23	63	11.4	2.17	40
1466838	0.26	0.66	83	211	5.18	123
1466839	0.21	0.49	67	8.1	4.42	65
1466840	0.07	0.36	66	1.9	2.45	53
1466841	0.18	0.59	86	2.8	5.61	63
1466842	0.03	0.17	11	0.4	0.89	8
1466501	0.09	0.49	77	0.5	4.56	77
1466502	0.08	0.56	52	0.4	3.62	72
1466503	0.11	0.73	93	0.3	4.04	65
1466504	0.09	0.43	44	0.2	2.65	52
1466505	0.11	0.37	50	0.3	2.91	66
1466506	0.10	0.55	67	0.4	3.58	71
1466507	0.19	0.56	76	0.2	6.67	101
1466508	0.18	0.83	77	0.2	6.93	76
1466509	0.17	0.50	95	0.2	5.44	97
1466510	0.19	0.66	97	0.2	8.60	109
1466511	0.18	0.71	75	0.2	8.96	91
1466512	0.16	0.75	76	0.2	8.93	128
1466513	0.14	0.97	66	0.2	12.8	84

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl	U	V	W	Y	Zn
	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B	GE_IMS14B
	0.02	0.05	1	0.1	0.05	1
	ppm	ppm	ppm	ppm	ppm	ppm
1466514	0.11	0.74	68	0.1	7.62	90
1466515	0.14	1.47	69	0.1	10.9	98
1466516	0.10	1.00	71	0.2	5.69	87
1466517	0.11	2.07	62	0.2	10.7	73
1466518	0.08	1.58	52	0.1	8.23	74
1466519	0.13	0.92	82	0.2	7.68	103
1466520	0.11	2.65	68	0.1	10.6	81
1466521	0.10	1.51	62	0.1	9.36	82
1466522	0.12	0.96	66	0.2	7.33	82
1466542	0.11	0.44	76	0.1	3.90	70
1466543	0.14	0.68	81	0.2	6.14	72
1466544	0.10	0.63	70	0.1	3.40	65
1466545	0.08	0.72	66	0.4	3.15	63
1466546	0.07	0.56	42	0.1	2.83	53
1466547	0.08	0.45	75	0.3	3.75	71
1466548	0.08	0.62	63	0.1	3.76	64
1466549	0.09	0.54	35	0.1	2.83	52
1466550	0.09	0.52	33	0.2	2.78	47
1467063	0.10	0.43	45	<0.1	2.89	40
1467064	0.10	0.57	68	0.1	6.27	63
1467065	0.11	0.63	80	0.1	5.75	79
1467066	0.12	0.64	79	0.1	6.25	69
1467067	0.15	1.71	84	0.3	13.1	102
1467068	0.26	0.58	92	<0.1	11.8	98
1467069	0.13	0.94	89	0.1	11.6	89
1467070	0.61	1.04	172	<0.1	19.4	155
1467071	0.23	0.50	87	<0.1	6.72	81
1467072	0.18	0.54	81	<0.1	7.84	98
1467073	0.15	0.66	90	0.1	7.56	84
1467074	0.16	0.95	99	<0.1	8.83	89
1467075	0.17	0.99	106	<0.1	9.54	93
1467101	0.06	0.50	30	0.3	2.65	28
1467102	0.18	2.63	81	0.2	10.5	153
1467103	0.09	0.80	45	0.1	4.01	77
1481101	0.18	1.13	88	0.1	10.7	119
1481102	0.10	0.74	55	<0.1	7.13	53

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .

Element Method Det.Lim. Units	Tl GE_IMS14B 0.02 ppm	U GE_IMS14B 0.05 ppm	V GE_IMS14B 1 ppm	W GE_IMS14B 0.1 ppm	Y GE_IMS14B 0.05 ppm	Zn GE_IMS14B 1 ppm
*Rep 1466815	0.28	1.02	49	0.4	5.17	54
*Rep 1466837	0.10	0.24	65	9.9	2.50	40
*Rep 1467067	0.14	1.70	82	0.1	12.9	100
*Std OREAS209	0.03	0.42	39	0.3	13.4	80
*Std OREAS151B	0.12	0.56	130	0.5	10.7	241
*Std OREAS209	0.03	0.42	38	0.3	12.6	77
*Bik BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1
*Bik BLANK	<0.02	<0.05	<1	<0.1	<0.05	<1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein.

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was (were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativity of the goods and strictly relate to the sample (s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law .