



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Submitted By: Jodie Gibson
Receiving Lab: Canada-Whitehorse
Received: August 09, 2017
Report Date: September 02, 2017
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI17000540.1

CLIENT JOB INFORMATION

Project: NOL
Shipment ID: NOL-20170807-002-RAB
P.O. Number
Number of Samples: 69

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.
Box 70
Dawson Yukon Y0B 1G0
Canada

CC: Isaac Fage
Shawn Ryan
Greg Dawson

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	66	Crush, split and pulverize 250 g rock to 200 mesh			WHI
SLBHP	3	Sort, label and box pulps			WHI
FA430	69	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	69	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	69	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	69	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 2 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1612104	Rock	4.56	0.006	0.7	24.0	47.5	128	0.2	26.7	13.9	975	4.03	51.5	3.9	7.7	22	0.5	12.2	0.3	96	1.62
1612105	Rock	2.73	0.021	1.1	27.9	251.1	138	0.6	24.4	15.2	967	3.92	185.9	20.5	7.0	38	0.7	8.6	0.5	78	3.91
1612106	Rock	3.19	0.011	1.3	75.5	50.0	226	0.6	25.4	17.9	868	4.23	235.6	7.4	7.2	12	1.7	14.5	2.1	90	0.85
1612107	Rock	2.82	0.011	1.3	104.2	119.4	184	0.9	30.4	24.6	1045	4.56	127.6	10.3	6.7	6	0.8	9.0	2.8	99	0.29
1612108	Rock	3.46	0.019	1.4	146.7	41.1	149	0.7	31.7	28.8	968	5.27	69.7	16.5	7.3	11	0.7	8.8	10.2	91	0.60
1612109	Rock	3.62	0.018	1.5	112.7	88.7	194	1.9	31.4	26.4	963	4.71	96.9	13.0	7.8	9	1.1	7.7	119.2	95	0.56
1612110	Rock	3.61	0.015	1.0	90.6	30.3	156	0.7	28.8	26.1	807	4.17	165.3	14.2	5.4	21	1.2	6.6	35.6	86	1.05
1612111	Rock	3.68	0.006	0.8	30.0	10.9	103	0.1	23.9	15.6	636	3.07	54.9	2.1	3.8	25	0.6	1.9	1.5	70	1.18
1612112	Rock	3.65	<0.005	1.0	27.8	47.4	139	0.2	25.5	13.9	836	3.66	68.0	0.9	5.0	24	0.8	3.7	1.1	87	1.55
1612113	Rock	3.54	<0.005	1.1	21.9	12.9	103	0.1	25.9	13.8	756	3.51	60.1	3.4	5.1	23	0.4	4.9	0.8	85	1.70
1612114	Rock	3.63	0.009	0.7	77.0	27.9	122	0.4	27.2	17.8	980	4.50	286.0	7.6	5.8	22	0.7	13.6	2.1	97	1.80
1612115	Rock	3.79	0.015	1.3	98.5	228.6	294	0.9	28.2	22.6	1148	5.79	523.8	12.2	6.4	13	2.8	17.8	1.5	109	0.67
1612116	Rock	4.50	0.006	0.7	25.3	45.2	142	0.2	24.6	13.3	652	3.24	116.8	3.7	4.6	25	1.1	2.8	0.3	84	2.01
1612117	Rock	4.00	<0.005	0.8	27.0	9.6	72	0.1	23.0	13.1	601	3.09	33.3	1.9	4.5	24	0.2	1.7	0.2	78	1.78
1612118	Rock	3.70	<0.005	0.8	21.4	9.1	59	0.1	23.2	13.9	606	3.03	142.8	2.5	4.7	27	0.2	2.3	0.2	77	1.84
1612119	Rock	3.81	<0.005	1.0	30.1	9.6	92	0.1	22.4	13.2	508	2.77	27.1	0.8	6.0	19	0.3	1.2	0.2	71	1.42
1612120	Rock Pulp	0.08	0.566	6.1	270.6	15.2	52	0.6	110.8	14.3	473	2.84	172.0	400.6	3.4	90	0.3	1.6	0.1	66	1.83
1612121	Rock	3.83	0.007	1.1	46.3	54.1	281	0.4	25.4	14.0	670	3.31	65.6	4.1	4.8	22	2.7	2.5	0.6	83	1.66
1612122	Rock	3.79	<0.005	1.0	14.3	14.8	171	<0.1	24.4	12.3	577	2.83	22.4	1.2	3.5	27	1.6	1.6	0.2	72	1.82
1612123	Rock	4.18	<0.005	1.1	19.4	8.3	54	<0.1	25.4	13.4	523	2.82	22.4	2.6	2.9	23	<0.1	0.8	0.2	69	1.42
1612124	Rock	3.79	<0.005	1.0	33.7	8.6	55	<0.1	24.0	13.9	529	2.84	15.2	0.8	2.8	19	0.3	0.8	0.1	72	1.27
1612125	Rock	3.62	0.012	1.0	30.8	20.0	72	0.1	24.5	15.6	599	3.08	38.0	1.9	3.5	23	0.3	1.1	0.5	75	1.46
1612126	Rock	3.90	<0.005	1.2	33.3	27.4	72	0.2	24.3	14.5	585	3.08	11.5	3.1	3.5	22	0.3	1.4	0.2	79	2.08
1612127	Rock	3.90	0.017	2.4	402.9	21.0	78	1.0	25.1	20.2	587	3.50	15.7	12.8	3.7	26	0.5	1.8	0.5	86	1.61
1612128	Rock	3.94	<0.005	1.9	68.0	8.9	52	0.2	18.4	11.7	492	2.52	13.9	2.1	2.5	20	0.2	2.0	0.2	59	1.46
1612129	Rock	4.10	0.007	1.1	83.1	10.9	74	0.2	25.3	14.0	681	3.36	28.8	4.2	3.5	23	0.3	6.4	0.3	87	1.79
1612130	Rock	4.06	<0.005	1.0	19.4	7.8	58	<0.1	24.1	13.8	707	3.49	10.4	2.1	3.9	24	<0.1	2.4	0.2	85	2.01
1612131	Rock	3.68	0.008	1.1	27.8	44.9	64	0.1	21.9	13.3	579	2.87	10.2	4.2	3.8	26	0.5	1.3	0.1	69	1.97
1612132	Rock	4.07	<0.005	1.2	28.4	41.3	74	0.1	21.1	13.1	515	2.83	5.2	3.8	3.9	21	0.4	1.0	0.1	68	1.50
1612133	Rock	3.99	0.024	1.2	79.9	11.0	64	0.2	22.7	14.1	586	2.99	11.8	12.2	4.7	20	0.2	1.4	0.2	70	1.59



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 2 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

		Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
			%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
			0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1612104	Rock		0.030	15	127	1.96	122	0.068	<20	2.48	0.028	0.18	0.3	<0.01	14.7	0.2	<0.05	9	<0.5	<0.2
1612105	Rock		0.027	17	89	1.56	86	0.015	<20	2.53	0.010	0.30	<0.1	0.01	11.2	0.3	<0.05	7	<0.5	<0.2
1612106	Rock		0.029	15	115	1.57	44	0.022	<20	2.25	0.015	0.26	0.2	<0.01	10.8	0.3	<0.05	8	<0.5	1.0
1612107	Rock		0.031	17	129	1.76	23	0.018	<20	2.44	0.009	0.24	0.2	<0.01	10.9	0.3	<0.05	9	<0.5	1.1
1612108	Rock		0.029	18	116	1.86	30	0.027	<20	2.75	0.015	0.30	0.3	<0.01	11.2	0.5	<0.05	9	<0.5	5.2
1612109	Rock		0.034	15	130	1.72	21	0.013	<20	2.53	0.014	0.25	0.2	<0.01	10.6	0.3	<0.05	9	<0.5	60.2
1612110	Rock		0.030	11	121	1.74	79	0.131	<20	2.24	0.042	0.37	0.6	<0.01	10.7	0.4	<0.05	8	<0.5	18.0
1612111	Rock		0.031	8	100	1.62	113	0.184	<20	1.93	0.049	0.49	0.6	<0.01	7.8	0.3	<0.05	6	<0.5	0.5
1612112	Rock		0.031	9	116	1.85	91	0.159	<20	2.25	0.049	0.41	0.6	<0.01	11.4	0.3	<0.05	8	<0.5	0.3
1612113	Rock		0.030	9	117	1.67	68	0.157	<20	1.98	0.042	0.29	0.6	<0.01	11.7	0.2	<0.05	7	0.5	0.5
1612114	Rock		0.029	12	121	1.79	48	0.129	<20	2.16	0.032	0.22	0.6	0.01	13.4	0.4	<0.05	9	<0.5	1.0
1612115	Rock		0.039	13	130	2.15	32	0.100	<20	2.75	0.014	0.21	0.7	<0.01	14.1	0.4	<0.05	11	<0.5	0.6
1612116	Rock		0.032	11	112	1.76	57	0.147	<20	2.03	0.060	0.26	0.7	<0.01	11.3	0.2	<0.05	7	<0.5	<0.2
1612117	Rock		0.030	8	104	1.59	52	0.151	<20	1.89	0.055	0.28	0.7	<0.01	9.9	0.2	<0.05	7	<0.5	<0.2
1612118	Rock		0.029	8	105	1.61	57	0.155	<20	1.99	0.059	0.29	0.6	<0.01	9.8	0.1	<0.05	7	<0.5	<0.2
1612119	Rock		0.031	8	100	1.43	59	0.155	<20	1.75	0.054	0.28	0.6	<0.01	8.4	0.1	<0.05	6	<0.5	<0.2
1612120	Rock Pulp		0.032	9	105	1.45	128	0.107	<20	2.76	0.326	0.21	1.1	0.03	3.4	<0.1	0.10	6	<0.5	<0.2
1612121	Rock		0.031	7	112	1.62	50	0.169	<20	1.98	0.055	0.23	0.7	<0.01	11.4	0.1	<0.05	8	<0.5	0.2
1612122	Rock		0.032	5	98	1.51	26	0.155	<20	1.88	0.042	0.15	0.6	<0.01	8.5	0.1	<0.05	7	<0.5	<0.2
1612123	Rock		0.033	4	95	1.46	74	0.165	<20	1.83	0.061	0.37	0.6	<0.01	7.3	0.1	<0.05	6	<0.5	<0.2
1612124	Rock		0.032	3	98	1.51	119	0.182	<20	1.94	0.060	0.60	0.5	<0.01	6.8	0.2	<0.05	6	<0.5	<0.2
1612125	Rock		0.032	5	101	1.55	84	0.167	<20	1.99	0.069	0.45	0.6	<0.01	8.7	0.2	<0.05	7	<0.5	<0.2
1612126	Rock		0.032	5	106	1.54	40	0.149	<20	1.88	0.055	0.22	0.8	<0.01	10.9	0.1	<0.05	7	<0.5	<0.2
1612127	Rock		0.029	5	112	1.71	83	0.170	<20	2.31	0.100	0.38	0.6	<0.01	10.8	0.3	<0.05	8	<0.5	<0.2
1612128	Rock		0.029	4	84	1.23	54	0.136	<20	1.52	0.065	0.23	1.2	<0.01	7.7	0.1	<0.05	6	<0.5	<0.2
1612129	Rock		0.033	8	117	1.71	82	0.170	<20	2.14	0.066	0.33	0.6	<0.01	11.0	0.2	<0.05	7	<0.5	<0.2
1612130	Rock		0.040	9	113	1.71	79	0.171	<20	2.13	0.051	0.37	0.7	<0.01	11.3	0.2	<0.05	7	<0.5	<0.2
1612131	Rock		0.029	7	99	1.42	77	0.172	<20	1.92	0.067	0.39	0.6	<0.01	8.2	0.2	<0.05	6	<0.5	<0.2
1612132	Rock		0.030	7	100	1.35	81	0.175	<20	1.88	0.066	0.46	0.9	<0.01	7.0	0.2	<0.05	6	<0.5	<0.2
1612133	Rock		0.033	9	103	1.40	95	0.180	<20	1.91	0.058	0.43	0.9	0.01	7.1	0.2	<0.05	7	<0.5	<0.2



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 3 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

	Method	Analyte	Unit	MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
					kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
					0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1612134	Rock				4.27	0.015	1.0	41.7	80.8	112	0.3	22.5	13.4	596	3.04	71.3	8.3	5.3	19	0.8	2.0	0.2	74	1.56
1612135	Rock				4.03	0.007	1.1	35.8	17.2	65	0.1	18.9	11.7	517	2.74	19.6	4.0	3.9	23	0.5	1.4	0.2	61	1.52
1612136	Rock				4.06	<0.005	1.1	40.0	5.9	49	0.1	21.4	13.3	517	2.70	12.7	4.3	4.0	23	<0.1	0.9	<0.1	65	1.72
1612137	Rock				4.05	0.005	0.9	62.7	8.5	71	0.2	17.6	11.3	450	2.41	11.8	2.7	3.2	18	0.2	1.0	0.1	53	1.30
1612138	Rock				3.76	0.009	1.0	22.6	5.1	47	0.1	19.2	12.1	488	2.63	162.9	6.8	3.1	19	<0.1	1.0	<0.1	62	1.60
1612139	Rock				4.02	<0.005	1.0	22.3	7.6	50	<0.1	20.8	12.6	492	2.67	20.9	1.1	2.7	19	0.2	0.5	<0.1	63	1.58
1612140	Rock Pulp				0.08	<0.005	2.0	21.4	2.1	41	0.3	19.9	8.8	383	2.22	4.8	<0.5	0.9	38	0.1	0.3	<0.1	52	0.72
1612141	Rock				4.07	<0.005	1.0	34.0	5.8	46	<0.1	19.2	11.4	459	2.56	16.7	1.0	3.3	17	0.1	0.8	0.1	56	1.39
1612142	Rock				4.47	<0.005	1.0	23.7	5.1	45	<0.1	19.8	11.9	491	2.66	15.4	2.8	3.6	18	<0.1	0.9	0.1	61	1.66
1612143	Rock				4.58	<0.005	1.4	25.1	4.8	46	<0.1	19.7	11.6	456	2.63	8.6	1.3	4.1	16	0.1	1.3	<0.1	58	1.28
1612144	Rock				2.45	0.005	1.5	27.9	7.0	67	0.1	20.5	11.0	590	3.25	58.8	3.4	5.5	18	<0.1	3.4	0.1	70	1.48
1612145	Rock				4.21	0.006	1.9	56.8	156.4	319	0.5	22.3	13.9	806	4.01	169.8	3.1	4.8	16	2.2	7.9	0.6	82	1.36
1612146	Rock				4.50	<0.005	1.3	27.9	22.6	121	0.1	18.9	11.6	450	2.37	70.4	2.2	2.9	18	0.4	1.4	<0.1	52	1.13
1612147	Rock				4.41	<0.005	1.5	29.7	5.3	53	<0.1	19.5	11.0	430	2.38	20.6	1.6	3.2	15	<0.1	1.2	<0.1	52	1.23
1612148	Rock				4.57	<0.005	1.4	30.4	4.8	71	<0.1	18.5	12.0	439	2.44	20.8	1.2	3.3	18	<0.1	1.0	<0.1	53	1.18
1612149	Rock				4.36	<0.005	1.2	31.4	5.8	46	<0.1	17.9	11.4	466	2.37	10.4	2.2	3.5	18	0.1	1.6	<0.1	53	1.37
1612150	Rock				4.70	<0.005	1.0	54.8	5.0	54	<0.1	17.5	10.7	439	2.42	45.7	2.2	3.6	19	0.2	1.5	<0.1	51	1.20
1612151	Rock				4.35	<0.005	1.8	47.5	6.8	76	0.2	18.9	11.5	482	2.62	50.0	3.3	3.6	15	0.2	3.0	0.1	57	1.16
1612152	Rock				4.77	0.006	1.8	43.0	159.1	204	0.4	22.0	14.2	746	3.42	73.2	3.6	4.1	15	1.7	11.5	0.3	75	1.31
1612153	Rock				4.24	0.014	8.4	49.2	84.2	157	0.7	21.0	34.9	848	5.82	60.5	9.3	6.3	10	1.2	6.5	1.8	70	0.41
1612154	Rock				4.62	0.006	1.7	28.7	30.7	106	0.2	20.6	16.4	660	2.98	49.7	4.0	4.3	17	0.7	5.4	0.3	69	1.38
1612155	Rock				4.39	0.014	1.5	39.1	339.2	273	1.1	21.0	13.7	816	3.21	521.8	11.6	4.4	15	2.0	8.1	0.3	76	1.60
1612156	Rock				4.65	0.006	1.7	24.8	17.8	114	0.2	19.3	11.5	566	2.55	182.0	3.1	4.1	18	0.4	2.2	0.1	55	1.33
1612157	Rock				2.66	<0.005	1.8	19.0	5.8	47	<0.1	20.3	11.9	482	2.59	20.2	1.0	3.5	17	<0.1	1.0	<0.1	57	1.08
1612158	Rock				4.44	<0.005	1.7	30.2	11.4	65	0.1	18.5	10.1	462	2.51	13.6	2.0	3.7	18	0.3	1.3	0.1	55	1.39
1612159	Rock				4.86	<0.005	1.9	17.6	3.4	34	<0.1	15.5	9.3	369	1.94	9.1	0.9	2.1	14	<0.1	1.1	<0.1	43	1.28
1612160	Rock Pulp				0.07	5.460	7.8	180.8	21.2	77	0.9	13.2	10.3	563	4.08	11.5	5008.0	2.6	76	<0.1	4.2	0.5	99	0.89
1612161	Rock				5.05	<0.005	2.0	10.2	3.1	40	<0.1	18.8	11.9	422	2.38	4.6	1.5	3.5	17	<0.1	1.0	<0.1	51	0.97
1612162	Rock				4.34	0.017	1.7	20.2	23.6	58	0.2	17.8	12.1	621	2.71	451.1	11.6	4.5	22	0.1	3.6	<0.1	57	1.78
1612163	Rock				4.35	<0.005	1.2	37.4	4.9	51	0.1	16.3	11.0	520	2.67	16.1	0.6	2.5	25	<0.1	1.6	<0.1	55	1.41



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 3 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

Method Analyte Unit MDL		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1612134	Rock	0.030	9	104	1.44	116	0.177	<20	2.00	0.061	0.53	0.7	<0.01	7.8	0.2	<0.05	7	<0.5	<0.2
1612135	Rock	0.040	7	85	1.28	97	0.166	<20	1.79	0.061	0.46	0.7	<0.01	6.4	0.2	<0.05	6	<0.5	<0.2
1612136	Rock	0.031	8	96	1.37	95	0.170	<20	1.83	0.070	0.46	0.7	<0.01	7.1	0.2	<0.05	6	<0.5	<0.2
1612137	Rock	0.027	5	80	1.26	125	0.137	<20	1.58	0.043	0.35	0.5	0.02	5.1	0.1	<0.05	5	<0.5	<0.2
1612138	Rock	0.028	5	86	1.40	86	0.136	<20	1.64	0.057	0.42	0.6	<0.01	7.1	0.2	<0.05	6	<0.5	<0.2
1612139	Rock	0.028	4	93	1.41	95	0.144	<20	1.66	0.054	0.48	0.7	<0.01	6.9	0.2	<0.05	6	<0.5	<0.2
1612140	Rock Pulp	0.054	4	25	0.72	88	0.104	<20	1.39	0.068	0.12	11.6	0.02	4.4	<0.1	<0.05	4	<0.5	<0.2
1612141	Rock	0.028	7	87	1.27	57	0.122	<20	1.57	0.050	0.28	0.8	<0.01	5.9	0.1	<0.05	6	<0.5	<0.2
1612142	Rock	0.027	6	90	1.31	67	0.138	<20	1.58	0.060	0.35	0.5	<0.01	7.1	0.1	<0.05	6	<0.5	<0.2
1612143	Rock	0.030	5	88	1.30	77	0.138	<20	1.61	0.050	0.39	0.7	<0.01	5.7	0.1	<0.05	6	<0.5	<0.2
1612144	Rock	0.025	7	96	1.40	58	0.133	<20	1.84	0.048	0.30	0.6	<0.01	8.1	0.1	<0.05	7	0.5	<0.2
1612145	Rock	0.026	8	107	1.64	40	0.113	<20	2.20	0.042	0.30	0.7	<0.01	10.2	0.2	<0.05	7	<0.5	<0.2
1612146	Rock	0.027	5	79	1.19	69	0.135	<20	1.60	0.060	0.36	0.5	<0.01	5.3	0.1	<0.05	5	<0.5	<0.2
1612147	Rock	0.027	6	81	1.20	78	0.132	<20	1.51	0.047	0.43	0.7	<0.01	4.6	0.2	<0.05	5	<0.5	<0.2
1612148	Rock	0.025	6	81	1.24	88	0.146	<20	1.58	0.065	0.42	0.9	<0.01	5.0	0.1	<0.05	5	<0.5	<0.2
1612149	Rock	0.028	5	77	1.17	58	0.133	<20	1.56	0.048	0.29	0.8	<0.01	5.3	<0.1	<0.05	5	<0.5	<0.2
1612150	Rock	0.024	7	76	1.21	102	0.148	<20	1.63	0.058	0.45	0.7	<0.01	4.4	0.2	<0.05	5	<0.5	<0.2
1612151	Rock	0.027	7	83	1.31	88	0.141	<20	1.67	0.052	0.47	0.8	<0.01	5.8	0.2	<0.05	5	<0.5	<0.2
1612152	Rock	0.028	7	102	1.56	74	0.134	<20	1.94	0.049	0.41	0.7	<0.01	10.3	0.3	<0.05	7	<0.5	<0.2
1612153	Rock	0.026	12	95	1.35	36	0.065	<20	2.19	0.017	0.37	0.4	<0.01	9.4	0.3	0.18	7	<0.5	<0.2
1612154	Rock	0.026	7	94	1.43	57	0.139	<20	1.82	0.053	0.31	0.7	<0.01	8.7	0.2	0.06	6	<0.5	<0.2
1612155	Rock	0.027	7	102	1.52	36	0.121	<20	1.76	0.035	0.21	0.8	<0.01	10.1	0.1	<0.05	7	<0.5	<0.2
1612156	Rock	0.027	5	81	1.31	56	0.141	<20	1.59	0.041	0.33	0.9	<0.01	6.1	0.1	<0.05	5	<0.5	<0.2
1612157	Rock	0.027	6	89	1.37	102	0.160	<20	1.71	0.059	0.55	1.0	<0.01	5.3	0.2	<0.05	5	<0.5	<0.2
1612158	Rock	0.028	6	87	1.21	41	0.132	<20	1.47	0.043	0.23	0.9	<0.01	5.6	0.1	<0.05	5	<0.5	<0.2
1612159	Rock	0.021	4	69	0.95	74	0.119	<20	1.14	0.044	0.35	2.2	<0.01	4.7	0.2	<0.05	4	<0.5	<0.2
1612160	Rock Pulp	0.054	7	17	0.86	133	0.133	<20	1.70	0.173	0.23	4.9	0.14	3.3	<0.1	<0.05	5	0.7	<0.2
1612161	Rock	0.028	6	84	1.22	113	0.157	<20	1.55	0.055	0.58	1.2	<0.01	4.1	0.2	<0.05	5	<0.5	<0.2
1612162	Rock	0.023	7	72	1.27	77	0.131	<20	1.63	0.047	0.34	1.1	<0.01	7.5	0.2	<0.05	6	<0.5	<0.2
1612163	Rock	0.051	5	65	1.23	64	0.153	<20	1.73	0.043	0.30	0.8	<0.01	5.1	0.1	<0.05	6	<0.5	<0.2



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 4 of 4

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1612164	Rock	3.19	<0.005	1.3	19.7	4.8	46	0.1	17.1	10.9	418	2.37	7.5	1.9	3.7	28	<0.1	1.8	<0.1	53	1.46
1612165	Rock	4.59	<0.005	1.5	32.3	27.9	69	0.1	21.1	12.8	592	2.66	30.0	1.2	4.1	26	0.2	2.1	<0.1	62	1.78
1612166	Rock	4.04	<0.005	1.2	24.5	5.0	50	0.1	22.5	14.7	627	3.20	12.2	1.1	4.2	27	<0.1	1.4	<0.1	80	2.18
1612167	Rock	4.33	<0.005	1.6	20.0	3.9	50	0.1	24.0	15.5	679	3.26	8.0	1.5	3.0	25	<0.1	0.7	<0.1	80	2.04
1612168	Rock	4.51	<0.005	1.4	24.5	4.6	59	<0.1	25.1	16.1	673	3.43	5.2	1.7	4.4	24	<0.1	4.2	<0.1	85	2.31
1612169	Rock	4.81	0.029	1.8	61.7	271.3	262	1.9	17.7	12.6	1255	3.48	726.2	25.2	4.2	59	2.2	19.8	0.2	64	8.01
1612170	Rock	4.41	0.015	1.4	59.7	335.6	400	3.0	19.6	13.9	1163	3.59	591.2	12.4	5.2	34	3.4	7.8	0.2	51	5.30
1612171	Rock	4.76	<0.005	1.3	16.9	15.3	66	0.2	25.7	16.1	706	3.24	51.2	2.6	4.2	20	0.2	2.5	<0.1	76	1.95
1612172	Rock	4.40	<0.005	1.4	19.7	8.9	54	0.1	20.8	12.4	552	2.68	17.9	2.8	3.7	24	0.2	2.3	<0.1	64	1.59



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 4 of 4

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000540.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1612164	Rock	0.024	6	76	1.19	49	0.148	<20	1.61	0.059	0.23	0.8	<0.01	5.5	<0.1	<0.05	6	<0.5	<0.2
1612165	Rock	0.027	7	92	1.37	46	0.141	<20	1.69	0.043	0.23	0.9	<0.01	7.9	0.1	<0.05	6	<0.5	<0.2
1612166	Rock	0.025	7	104	1.80	58	0.149	<20	2.01	0.036	0.35	0.7	<0.01	11.7	0.1	<0.05	7	<0.5	<0.2
1612167	Rock	0.029	6	108	1.89	91	0.132	<20	1.99	0.039	0.56	0.5	<0.01	11.0	0.2	<0.05	6	<0.5	<0.2
1612168	Rock	0.028	6	114	2.10	88	0.126	<20	2.22	0.033	0.54	0.4	<0.01	12.6	0.2	<0.05	7	<0.5	<0.2
1612169	Rock	0.021	9	81	1.80	48	0.048	<20	1.95	0.015	0.31	0.5	0.01	10.5	0.2	<0.05	6	<0.5	<0.2
1612170	Rock	0.022	13	61	1.15	30	0.002	<20	2.17	0.004	0.25	0.6	0.02	10.2	0.2	<0.05	4	<0.5	<0.2
1612171	Rock	0.028	8	106	1.84	57	0.089	<20	2.06	0.025	0.34	0.5	<0.01	11.8	0.2	<0.05	7	<0.5	<0.2
1612172	Rock	0.028	7	96	1.47	55	0.138	<20	1.88	0.045	0.28	0.8	<0.01	7.8	0.1	<0.05	6	<0.5	<0.2



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

NOL

Report Date:

September 02, 2017

Page:

1 of 2

Part:

1 of 2

QUALITY CONTROL REPORT

WHI17000540.1

Method Analyte Unit MDL		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
Pulp Duplicates																					
1612105	Rock	2.73	0.021	1.1	27.9	251.1	138	0.6	24.4	15.2	967	3.92	185.9	20.5	7.0	38	0.7	8.6	0.5	78	3.91
REP 1612105	QC			1.0	27.8	246.1	139	0.6	24.1	15.5	965	3.94	185.5	20.0	6.9	38	0.7	8.8	0.5	78	3.86
1612132	Rock	4.07	<0.005	1.2	28.4	41.3	74	0.1	21.1	13.1	515	2.83	5.2	3.8	3.9	21	0.4	1.0	0.1	68	1.50
REP 1612132	QC		<0.005																		
REP 1612138	QC			1.1	22.6	5.1	45	0.1	19.0	11.8	476	2.56	166.1	8.0	2.9	17	<0.1	1.1	<0.1	59	1.56
1612162	Rock	4.34	0.017	1.7	20.2	23.6	58	0.2	17.8	12.1	621	2.71	451.1	11.6	4.5	22	0.1	3.6	<0.1	57	1.78
REP 1612162	QC		0.017																		
Core Reject Duplicates																					
1612104	Rock	4.56	0.006	0.7	24.0	47.5	128	0.2	26.7	13.9	975	4.03	51.5	3.9	7.7	22	0.5	12.2	0.3	96	1.62
DUP 1612104	QC		0.007	0.9	21.9	43.0	121	0.2	26.0	13.7	935	3.87	46.7	4.0	7.0	21	0.4	12.1	0.3	93	1.54
1612138	Rock	3.76	0.009	1.0	22.6	5.1	47	0.1	19.2	12.1	488	2.63	162.9	6.8	3.1	19	<0.1	1.0	<0.1	62	1.60
DUP 1612138	QC		0.010	0.9	22.2	5.0	44	0.1	19.1	11.3	466	2.55	165.8	7.6	3.0	17	<0.1	1.0	<0.1	58	1.53
1612172	Rock	4.40	<0.005	1.4	19.7	8.9	54	0.1	20.8	12.4	552	2.68	17.9	2.8	3.7	24	0.2	2.3	<0.1	64	1.59
DUP 1612172	QC		<0.005	1.6	19.9	8.8	54	0.1	20.6	12.7	551	2.68	18.2	1.0	3.7	23	<0.1	2.0	<0.1	62	1.55
Reference Materials																					
STD DS11	Standard			11.5	137.1	126.8	326	2.1	73.8	13.0	999	3.00	44.5	500.7	7.2	68	2.3	7.6	12.0	46	0.99
STD DS11	Standard			10.5	137.1	126.2	317	1.6	72.3	11.8	951	2.87	39.8	50.6	6.6	63	2.2	7.9	11.1	44	0.95
STD DS11	Standard			13.6	146.0	137.5	338	1.4	75.2	13.2	1014	3.01	42.4	53.7	7.6	71	2.7	7.4	12.4	48	1.00
STD OREAS45EA	Standard			1.4	652.9	11.7	29	0.2	345.7	47.3	402	21.40	10.8	51.0	8.3	4	<0.1	0.4	0.2	299	0.03
STD OREAS45EA	Standard			1.2	644.8	11.9	29	0.2	345.9	47.9	400	21.72	10.4	46.4	8.5	4	<0.1	0.4	0.2	299	0.03
STD OREAS45EA	Standard			1.4	681.2	13.3	29	0.2	362.7	49.1	394	20.84	11.0	42.6	9.4	4	<0.1	0.3	0.3	297	0.03
STD OXC145	Standard		0.215																		
STD OXH122	Standard		1.252																		
STD OXN117	Standard		7.824																		
STD OXN117 Expected			7.679																		
STD OXC145 Expected			0.212																		
STD OXH122 Expected			1.247																		
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

NOL

Report Date:

September 02, 2017

Page:

1 of 2

Part:

2 of 2

QUALITY CONTROL REPORT

WHI17000540.1

		Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																				
1612105	Rock	0.027	17	89	1.56	86	0.015	<20	2.53	0.010	0.30	<0.1	0.01	11.2	0.3	<0.05	7	<0.5	<0.2	
REP 1612105	QC	0.027	17	88	1.55	84	0.014	<20	2.54	0.010	0.30	<0.1	0.01	11.0	0.3	<0.05	7	<0.5	<0.2	
1612132	Rock	0.030	7	100	1.35	81	0.175	<20	1.88	0.066	0.46	0.9	<0.01	7.0	0.2	<0.05	6	<0.5	<0.2	
REP 1612132	QC																			
REP 1612138	QC	0.028	4	83	1.37	82	0.126	<20	1.57	0.044	0.40	0.6	<0.01	6.6	0.2	<0.05	6	<0.5	<0.2	
1612162	Rock	0.023	7	72	1.27	77	0.131	<20	1.63	0.047	0.34	1.1	<0.01	7.5	0.2	<0.05	6	<0.5	<0.2	
REP 1612162	QC																			
Core Reject Duplicates																				
1612104	Rock	0.030	15	127	1.96	122	0.068	<20	2.48	0.028	0.18	0.3	<0.01	14.7	0.2	<0.05	9	<0.5	<0.2	
DUP 1612104	QC	0.030	14	122	1.91	104	0.066	<20	2.40	0.025	0.17	0.3	0.01	14.4	0.1	<0.05	8	<0.5	<0.2	
1612138	Rock	0.028	5	86	1.40	86	0.136	<20	1.64	0.057	0.42	0.6	<0.01	7.1	0.2	<0.05	6	<0.5	<0.2	
DUP 1612138	QC	0.029	5	83	1.35	80	0.127	<20	1.56	0.043	0.39	0.6	<0.01	6.6	0.1	<0.05	5	<0.5	<0.2	
1612172	Rock	0.028	7	96	1.47	55	0.138	<20	1.88	0.045	0.28	0.8	<0.01	7.8	0.1	<0.05	6	<0.5	<0.2	
DUP 1612172	QC	0.026	7	95	1.46	52	0.138	<20	1.85	0.038	0.27	0.8	<0.01	7.8	0.1	<0.05	6	<0.5	<0.2	
Reference Materials																				
STD DS11	Standard	0.069	18	54	0.83	425	0.085	<20	1.09	0.068	0.39	2.8	0.24	3.2	5.1	0.26	5	2.2	5.0	
STD DS11	Standard	0.064	16	51	0.78	389	0.079	<20	1.02	0.063	0.37	2.3	0.22	3.0	4.8	0.26	4	1.8	4.4	
STD DS11	Standard	0.069	19	56	0.87	438	0.092	<20	1.12	0.072	0.39	3.0	0.28	3.2	5.1	0.25	5	1.6	4.5	
STD OREAS45EA	Standard	0.027	6	732	0.10	128	0.089	<20	2.86	0.018	0.05	<0.1	0.01	76.8	<0.1	<0.05	12	1.2	<0.2	
STD OREAS45EA	Standard	0.029	6	727	0.09	132	0.088	<20	2.89	0.018	0.05	<0.1	<0.01	76.2	<0.1	<0.05	12	1.2	<0.2	
STD OREAS45EA	Standard	0.029	7	738	0.10	138	0.098	<20	3.23	0.018	0.05	<0.1	<0.01	79.3	<0.1	<0.05	12	1.7	<0.2	
STD OXC145	Standard																			
STD OXH122	Standard																			
STD OXN117	Standard																			
STD OXN117 Expected																				
STD OXC145 Expected																				
STD OXH122 Expected																				
STD OREAS45EA Expected			0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053		78	0.072	0.036	12.4	0.78	0.07	



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI17000540.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD DS11 Expected				13.9	156	138	345	1.71	81.9	14.2	1055	3.2082	42.8	79	7.65	67.3	2.37	7.2	12.2	50	1.063
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.8	6.5	54.8	94	0.1	1.1	3.8	555	1.79	2.7	0.5	2.1	25	0.4	1.2	<0.1	23	0.55
ROCK-WHI	Prep Blank		<0.005	0.7	4.6	17.4	47	<0.1	0.7	3.6	533	1.66	1.8	1.9	2.2	20	0.2	0.7	<0.1	20	0.49



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: NOL
Report Date: September 02, 2017

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17000540.1

		AQ200 P % 0.001	AQ200 La ppm 1	AQ200 Cr ppm 1	AQ200 Mg % 0.01	AQ200 Ba ppm 1	AQ200 Ti % 0.001	AQ200 B ppm 20	AQ200 Al % 0.01	AQ200 Na % 0.001	AQ200 K % 0.01	AQ200 W ppm 0.1	AQ200 Hg ppm 0.01	AQ200 Sc ppm 0.1	AQ200 Tl ppm 0.1	AQ200 S % 0.05	AQ200 Ga ppm 1	AQ200 Se ppm 0.5	AQ200 Te ppm 0.2
STD DS11 Expected		0.0701	18.6	61.5	0.85	417	0.0976		1.129	0.0694	0.4	2.9	0.3	3.1	4.9	0.2835	4.7	1.9	4.56
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.041	5	2	0.51	362	0.086	<20	0.87	0.060	0.08	<0.1	0.03	2.6	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.038	5	2	0.47	109	0.079	<20	0.80	0.072	0.08	<0.1	<0.01	2.7	<0.1	<0.05	4	<0.5	<0.2