



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Submitted By: Jodie Gibson
Receiving Lab: Canada-Whitehorse
Received: September 08, 2017
Report Date: October 11, 2017
Page: 1 of 3

CERTIFICATE OF ANALYSIS

WHI17000799.1

CLIENT JOB INFORMATION

Project: BRW
Shipment ID: BRW-20170904-001-RAB
P.O. Number
Number of Samples: 40

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

| Procedure Code | Number of Samples | Code Description | Test Wgt (g) | Report Status | Lab |
|----------------|-------------------|---|--------------|---------------|-----|
| PRP70-250 | 38 | Crush, split and pulverize 250 g rock to 200 mesh | | | WHI |
| SPTRF | 1 | Split samples by riffle splitter | | | VAN |
| PUL85 | 1 | Pulverize to 85% passing 200 mesh | | | VAN |
| SLBHP | 1 | Sort, label and box pulps | | | WHI |
| FA430 | 40 | Lead Collection Fire - Assay Fusion - AAS Finish | 30 | Completed | VAN |
| EN002 | 40 | Environmental disposal charge-Fire assay lead waste | | | VAN |
| AQ200 | 40 | 1:1:1 Aqua Regia digestion ICP-MS analysis | 0.5 | Completed | VAN |
| SHP01 | 40 | Per sample shipping charges for branch shipments | | | VAN |

ADDITIONAL COMMENTS

Invoice To: Ground Truth Exploration Inc.
Box 70
Dawson Yukon Y0B 1G0
Canada

CC: Isaac Fage
Shawn Ryan
Greg Dawson



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BRW
Report Date: October 11, 2017

Page: 2 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000799.1

| | Method Analyte Unit MDL | WGHT | FA430 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|
| | | Wgt | Au | Mo | Cu | Pb | Zn | Ag | Ni | Co | Mn | Fe | As | Au | Th | Sr | Cd | Sb | Bi | V | Ca |
| | | kg | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | % | ppm | ppb | ppm | ppm | ppm | ppm | ppm | ppm | % |
| | | 0.01 | 0.005 | 0.1 | 0.1 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 1 | 0.01 | 0.5 | 0.5 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 2 | 0.01 |
| 1612623 | Rock | 3.89 | <0.005 | 1.8 | 83.0 | 9.6 | 47 | 0.1 | 13.9 | 4.8 | 233 | 1.65 | 12.6 | 1.1 | 9.5 | 9 | 0.2 | 0.2 | 0.1 | 35 | 0.04 |
| 1612624 | Rock | 3.51 | <0.005 | 4.1 | 78.0 | 8.8 | 41 | 0.2 | 15.3 | 6.5 | 327 | 1.67 | 10.9 | 1.6 | 9.9 | 14 | 0.2 | 0.3 | <0.1 | 43 | 0.04 |
| 1612625 | Rock | 3.43 | 0.006 | 7.4 | 59.4 | 5.6 | 14 | 0.2 | 8.7 | 1.4 | 80 | 1.18 | 12.5 | 2.7 | 4.6 | 9 | 0.1 | 0.2 | <0.1 | 36 | 0.02 |
| 1612626 | Rock | 3.28 | <0.005 | 3.8 | 115.9 | 6.2 | 39 | 0.3 | 21.9 | 2.0 | 79 | 2.10 | 16.8 | 1.8 | 6.4 | 12 | 0.4 | 0.3 | 0.1 | 39 | 0.02 |
| 1612627 | Rock | 3.85 | <0.005 | 3.7 | 112.4 | 6.8 | 42 | 0.2 | 11.9 | 2.1 | 102 | 2.55 | 19.6 | 1.4 | 7.0 | 12 | 0.6 | 0.6 | 0.1 | 40 | 0.02 |
| 1612603 | Rock | 3.44 | 0.023 | 2.4 | 29.7 | 10.4 | 12 | 0.1 | 4.1 | 0.5 | 34 | 1.56 | 44.1 | 14.4 | 7.0 | 26 | <0.1 | 0.5 | 0.1 | 29 | 0.03 |
| 1612604 | Rock | 3.46 | 0.006 | 2.2 | 34.6 | 9.6 | 9 | 0.1 | 2.9 | 0.4 | 21 | 1.57 | 47.9 | 1.9 | 9.7 | 10 | <0.1 | 0.3 | 0.1 | 37 | 0.01 |
| 1612605 | Rock | 3.23 | 0.015 | 2.2 | 22.4 | 16.5 | 6 | 0.1 | 3.1 | 0.5 | 27 | 1.16 | 45.7 | 6.7 | 9.5 | 13 | <0.1 | 0.4 | 0.1 | 30 | 0.02 |
| 1612606 | Rock | 3.07 | 0.138 | 2.5 | 16.2 | 11.0 | 5 | 0.1 | 3.0 | 0.5 | 27 | 1.09 | 43.8 | 31.4 | 8.0 | 14 | <0.1 | 0.3 | 0.1 | 18 | 0.03 |
| 1612607 | Rock | 3.52 | 0.015 | 5.4 | 14.4 | 23.0 | 24 | 0.3 | 5.6 | 0.8 | 44 | 1.94 | 24.7 | 7.3 | 3.9 | 16 | <0.1 | 1.4 | 0.2 | 25 | 0.02 |
| 1612578 | Rock | 3.78 | 0.052 | 8.0 | 78.6 | 84.4 | 39 | 0.2 | 21.4 | 3.5 | 44 | 1.25 | 53.3 | 42.5 | 1.5 | 15 | 0.2 | 6.9 | 0.2 | 10 | 0.01 |
| 1612579 | Rock | 3.15 | 0.065 | 7.2 | 59.5 | 84.6 | 50 | 0.2 | 32.4 | 4.3 | 47 | 1.58 | 23.6 | 47.6 | 2.1 | 22 | 0.2 | 3.2 | 0.1 | 19 | 0.01 |
| 1612580 | Rock Pulp | 0.10 | 5.313 | 8.7 | 196.4 | 21.4 | 77 | 1.0 | 15.9 | 11.5 | 615 | 4.44 | 12.1 | 6189.4 | 2.7 | 76 | 0.2 | 3.3 | 0.4 | 111 | 0.97 |
| 1612581 | Rock | 3.33 | 0.025 | 5.9 | 70.7 | 25.5 | 31 | 0.1 | 10.4 | 1.8 | 30 | 1.43 | 30.3 | 22.3 | 4.8 | 7 | <0.1 | 2.0 | 0.1 | 12 | 0.01 |
| 1612582 | Rock | 3.38 | 0.061 | 10.2 | 46.3 | 22.3 | 45 | 0.2 | 25.3 | 6.9 | 55 | 1.69 | 26.0 | 35.4 | 1.6 | 6 | 0.1 | 3.0 | 0.1 | 13 | <0.01 |
| 1612613 | Rock | 3.27 | 0.006 | 3.0 | 49.3 | 11.8 | 27 | 0.2 | 5.8 | 2.5 | 89 | 1.37 | 45.0 | 5.0 | 8.4 | 10 | <0.1 | 0.7 | 0.1 | 33 | 0.05 |
| 1612614 | Rock | 4.02 | 0.009 | 5.5 | 66.4 | 9.2 | 41 | 0.4 | 8.7 | 1.2 | 39 | 2.53 | 50.4 | 5.0 | 4.5 | 8 | 0.1 | 1.3 | 0.1 | 43 | 0.01 |
| 1612615 | Rock | 3.13 | 0.006 | 6.3 | 42.0 | 5.3 | 12 | 0.4 | 3.4 | 0.6 | 26 | 1.25 | 34.4 | 2.1 | 3.5 | 6 | <0.1 | 0.7 | 0.1 | 21 | <0.01 |
| 1612616 | Rock | 3.73 | 0.007 | 5.3 | 42.8 | 6.4 | 26 | 0.3 | 7.2 | 0.9 | 55 | 1.60 | 32.3 | 2.5 | 4.4 | 7 | <0.1 | 0.6 | <0.1 | 23 | 0.01 |
| 1612617 | Rock | 3.62 | 0.007 | 2.2 | 68.0 | 8.2 | 27 | 0.2 | 7.5 | 1.0 | 124 | 1.85 | 12.0 | 3.3 | 6.4 | 8 | <0.1 | 0.3 | 0.1 | 32 | 0.02 |
| 1612593 | Rock | 3.75 | 0.059 | 6.2 | 49.5 | 9.4 | 40 | 0.5 | 14.7 | 1.0 | 44 | 1.82 | 27.7 | 42.8 | 1.3 | 7 | <0.1 | 2.0 | 0.2 | 11 | 0.01 |
| 1612594 | Rock | 3.37 | 0.071 | 9.3 | 52.0 | 12.3 | 57 | 0.4 | 14.1 | 1.1 | 47 | 2.21 | 31.4 | 58.6 | 1.4 | 7 | <0.1 | 2.8 | 0.2 | 25 | 0.01 |
| 1612595 | Rock | 3.47 | 0.034 | 5.5 | 37.8 | 23.4 | 63 | 0.3 | 16.2 | 1.1 | 46 | 2.07 | 27.1 | 23.4 | 0.9 | 6 | <0.1 | 3.3 | 0.1 | 19 | 0.01 |
| 1612596 | Rock | 3.71 | 0.048 | 5.4 | 78.3 | 58.9 | 97 | 0.7 | 24.8 | 1.6 | 64 | 3.03 | 34.3 | 31.4 | 1.9 | 13 | <0.1 | 4.3 | 0.2 | 19 | 0.01 |
| 1612597 | Rock | 3.28 | 0.023 | 4.5 | 83.3 | 69.5 | 20 | 0.7 | 11.0 | 2.6 | 97 | 1.12 | 69.9 | 29.7 | 2.2 | 8 | 0.1 | 4.1 | 0.1 | 9 | 0.01 |
| 1612598 | Rock | 3.43 | 0.025 | 6.9 | 116.9 | 406.5 | 105 | 0.6 | 25.7 | 3.0 | 132 | 2.73 | 61.3 | 12.6 | 2.2 | 23 | 0.2 | 5.0 | 0.2 | 26 | 0.02 |
| 1612599 | Rock | 3.25 | 0.019 | 7.2 | 60.8 | 288.6 | 86 | 0.5 | 20.8 | 1.6 | 96 | 1.94 | 31.2 | 7.8 | 1.4 | 20 | <0.1 | 3.3 | 0.2 | 35 | 0.02 |
| 1612600 | Silica | 0.23 | 0.005 | 0.5 | 3.3 | 4.6 | 23 | 0.1 | 2.1 | 0.5 | 118 | 0.19 | 3.5 | 2.2 | 0.2 | 310 | 0.3 | 1.3 | <0.1 | 23 | 21.13 |
| 1612601 | Rock | 3.21 | 0.017 | 6.8 | 28.4 | 143.7 | 96 | 0.5 | 16.2 | 0.8 | 84 | 1.87 | 21.2 | 9.1 | 1.4 | 15 | <0.1 | 3.4 | 0.2 | 29 | 0.02 |
| 1612602 | Rock | 3.83 | 0.020 | 10.3 | 28.1 | 53.2 | 133 | 0.3 | 25.4 | 1.4 | 56 | 4.94 | 72.2 | 10.3 | 3.9 | 25 | 0.2 | 2.4 | 0.2 | 33 | 0.02 |



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BRW
Report Date: October 11, 2017

Page: 2 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000799.1

| | Method | Analyte | Unit | MDL | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | | | |
|---------|-----------|---------|------|-----|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-----|------|------|
| | | | | | P | La | Cr | Mg | Ba | Ti | B | Al | Na | K | W | Hg | Sc | Tl | S | Ga | Se | Te |
| | | | | | % | ppm | ppm | % | ppm | % | ppm | % | % | % | ppm | ppm | ppm | ppm | % | ppm | ppm | ppm |
| | | | | | 0.001 | 1 | 1 | 0.01 | 1 | 0.001 | 20 | 0.01 | 0.001 | 0.01 | 0.1 | 0.01 | 0.1 | 0.1 | 0.05 | 1 | 0.5 | 0.2 |
| 1612623 | Rock | | | | 0.033 | 23 | 26 | 0.36 | 418 | 0.091 | <20 | 1.04 | 0.005 | 0.57 | 0.1 | 0.01 | 6.7 | 0.5 | <0.05 | 3 | <0.5 | <0.2 |
| 1612624 | Rock | | | | 0.036 | 29 | 27 | 0.31 | 510 | 0.076 | <20 | 1.05 | 0.004 | 0.53 | 0.3 | 0.02 | 7.0 | 0.5 | 0.06 | 3 | 1.1 | <0.2 |
| 1612625 | Rock | | | | 0.023 | 13 | 21 | 0.07 | 256 | 0.009 | <20 | 0.35 | 0.003 | 0.19 | 0.9 | 0.02 | 2.6 | 0.1 | 0.05 | <1 | 1.8 | <0.2 |
| 1612626 | Rock | | | | 0.049 | 14 | 21 | 0.09 | 459 | 0.010 | <20 | 0.57 | 0.005 | 0.22 | 0.4 | 0.03 | 4.0 | 0.2 | <0.05 | 1 | 1.4 | <0.2 |
| 1612627 | Rock | | | | 0.058 | 21 | 26 | 0.13 | 361 | 0.022 | <20 | 0.49 | 0.006 | 0.31 | 0.4 | 0.03 | 2.5 | 0.4 | 0.12 | 2 | 8.6 | <0.2 |
| 1612603 | Rock | | | | 0.032 | 18 | 21 | 0.02 | 562 | 0.001 | <20 | 0.30 | 0.005 | 0.16 | 0.2 | 0.02 | 2.2 | <0.1 | <0.05 | 2 | 2.8 | <0.2 |
| 1612604 | Rock | | | | 0.021 | 23 | 27 | 0.01 | 233 | 0.002 | <20 | 0.29 | 0.005 | 0.15 | <0.1 | <0.01 | 2.4 | <0.1 | <0.05 | 2 | 1.1 | <0.2 |
| 1612605 | Rock | | | | 0.014 | 21 | 20 | 0.02 | 182 | 0.001 | <20 | 0.25 | 0.004 | 0.14 | 0.2 | 0.02 | 1.8 | <0.1 | <0.05 | 1 | 0.9 | <0.2 |
| 1612606 | Rock | | | | 0.014 | 19 | 23 | 0.03 | 225 | 0.001 | <20 | 0.29 | 0.004 | 0.17 | <0.1 | 0.02 | 2.7 | <0.1 | <0.05 | 2 | 0.8 | <0.2 |
| 1612607 | Rock | | | | 0.026 | 8 | 23 | 0.02 | 324 | 0.002 | <20 | 0.20 | 0.003 | 0.14 | 0.5 | 0.07 | 2.1 | <0.1 | <0.05 | 1 | 2.5 | <0.2 |
| 1612578 | Rock | | | | 0.011 | 5 | 10 | 0.01 | 998 | <0.001 | <20 | 0.18 | 0.002 | 0.09 | 1.6 | 0.17 | 1.5 | <0.1 | <0.05 | <1 | 1.0 | <0.2 |
| 1612579 | Rock | | | | 0.019 | 8 | 19 | 0.01 | 216 | 0.001 | <20 | 0.25 | 0.003 | 0.11 | 0.9 | 0.11 | 1.6 | <0.1 | <0.05 | <1 | 1.5 | <0.2 |
| 1612580 | Rock Pulp | | | | 0.057 | 7 | 21 | 0.89 | 138 | 0.165 | <20 | 1.79 | 0.186 | 0.24 | 4.5 | 0.16 | 3.4 | <0.1 | <0.05 | 5 | <0.5 | <0.2 |
| 1612581 | Rock | | | | 0.016 | 13 | 10 | <0.01 | 153 | 0.001 | <20 | 0.23 | 0.003 | 0.12 | 0.6 | 0.15 | 1.5 | <0.1 | <0.05 | <1 | 4.1 | <0.2 |
| 1612582 | Rock | | | | 0.016 | 5 | 12 | <0.01 | 838 | <0.001 | <20 | 0.17 | 0.002 | 0.07 | 1.7 | 0.10 | 1.4 | <0.1 | <0.05 | <1 | 1.3 | <0.2 |
| 1612613 | Rock | | | | 0.021 | 19 | 40 | 0.35 | 976 | 0.049 | <20 | 0.85 | 0.004 | 0.39 | <0.1 | 0.05 | 8.8 | 0.4 | <0.05 | 3 | <0.5 | <0.2 |
| 1612614 | Rock | | | | 0.031 | 12 | 23 | 0.03 | 642 | 0.004 | <20 | 0.23 | 0.004 | 0.14 | 0.4 | 0.08 | 2.8 | 0.1 | 0.07 | 1 | 1.6 | <0.2 |
| 1612615 | Rock | | | | 0.011 | 9 | 15 | 0.02 | 565 | 0.002 | <20 | 0.19 | 0.004 | 0.11 | 0.4 | 0.16 | 1.1 | <0.1 | <0.05 | <1 | 1.8 | <0.2 |
| 1612616 | Rock | | | | 0.028 | 12 | 26 | 0.08 | 738 | 0.012 | <20 | 0.28 | 0.004 | 0.19 | 0.5 | 0.07 | 2.7 | 0.1 | 0.08 | 2 | 2.3 | <0.2 |
| 1612617 | Rock | | | | 0.029 | 11 | 33 | 0.27 | 895 | 0.060 | <20 | 0.67 | 0.004 | 0.44 | <0.1 | 0.03 | 3.4 | 0.4 | 0.06 | 3 | 1.9 | <0.2 |
| 1612593 | Rock | | | | 0.019 | 3 | 11 | <0.01 | 353 | 0.001 | <20 | 0.20 | 0.001 | 0.09 | 1.1 | 0.31 | 1.1 | <0.1 | <0.05 | <1 | 3.3 | 0.2 |
| 1612594 | Rock | | | | 0.028 | 2 | 18 | 0.01 | 225 | 0.002 | <20 | 0.19 | 0.003 | 0.10 | 1.1 | 0.49 | 1.1 | <0.1 | <0.05 | <1 | 6.9 | 0.2 |
| 1612595 | Rock | | | | 0.029 | 2 | 17 | <0.01 | 189 | 0.001 | <20 | 0.17 | 0.001 | 0.06 | 0.9 | 0.32 | 1.5 | <0.1 | <0.05 | <1 | 3.9 | <0.2 |
| 1612596 | Rock | | | | 0.039 | 7 | 15 | <0.01 | 887 | 0.002 | <20 | 0.20 | 0.002 | 0.09 | 1.8 | 0.65 | 1.3 | <0.1 | <0.05 | <1 | 5.9 | <0.2 |
| 1612597 | Rock | | | | 0.016 | 6 | 12 | <0.01 | 483 | 0.002 | <20 | 0.16 | 0.002 | 0.07 | 1.5 | 0.45 | 0.7 | 0.1 | <0.05 | <1 | 4.0 | <0.2 |
| 1612598 | Rock | | | | 0.055 | 6 | 19 | 0.01 | 265 | 0.002 | <20 | 0.24 | 0.001 | 0.08 | 1.2 | 0.51 | 1.4 | 0.1 | <0.05 | <1 | 5.1 | <0.2 |
| 1612599 | Rock | | | | 0.039 | 4 | 20 | 0.01 | 214 | <0.001 | <20 | 0.22 | 0.001 | 0.10 | 0.8 | 0.25 | 2.4 | <0.1 | <0.05 | 1 | 5.6 | <0.2 |
| 1612600 | Silica | | | | 0.025 | 2 | 4 | 13.21 | 19 | 0.002 | <20 | 0.10 | 0.001 | 0.01 | 0.2 | 0.01 | 0.6 | <0.1 | <0.05 | <1 | <0.5 | <0.2 |
| 1612601 | Rock | | | | 0.033 | 4 | 15 | <0.01 | 231 | 0.001 | <20 | 0.18 | 0.002 | 0.09 | 0.8 | 0.22 | 2.1 | <0.1 | <0.05 | <1 | 2.9 | <0.2 |
| 1612602 | Rock | | | | 0.138 | 13 | 21 | 0.01 | 498 | 0.002 | <20 | 0.26 | 0.002 | 0.12 | 0.6 | 0.09 | 3.2 | <0.1 | <0.05 | 1 | 2.6 | <0.2 |



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BRW
Report Date: October 11, 2017

Page: 3 of 3

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000799.1

| | Method | WGHT | FA430 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|---------|------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | Analyte | Wgt | Au | Mo | Cu | Pb | Zn | Ag | Ni | Co | Mn | Fe | As | Au | Th | Sr | Cd | Sb | Bi | V | Ca |
| | Unit | kg | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | % | ppm | ppb | ppm | ppm | ppm | ppm | ppm | ppm | % |
| | MDL | 0.01 | 0.005 | 0.1 | 0.1 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 1 | 0.01 | 0.5 | 0.5 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 2 | 0.01 |
| 1612573 | Rock | 3.05 | 0.134 | 5.3 | 40.5 | 16.1 | 22 | <0.1 | 16.0 | 3.0 | 41 | 1.10 | 9.8 | 101.4 | 2.0 | 9 | <0.1 | 3.5 | <0.1 | 8 | 0.01 |
| 1612574 | Rock | 4.81 | 0.138 | 3.4 | 45.1 | 4.0 | 19 | <0.1 | 12.5 | 5.2 | 110 | 1.17 | 12.3 | 134.5 | 1.9 | 7 | <0.1 | 4.5 | <0.1 | 9 | 0.01 |
| 1612575 | Rock | 3.19 | 0.531 | 2.8 | 34.9 | 2.1 | 8 | 0.1 | 6.2 | 2.7 | 45 | 0.75 | 6.1 | 682.8 | 1.4 | 3 | <0.1 | 3.0 | <0.1 | 5 | <0.01 |
| 1612576 | Rock | 3.51 | 0.304 | 4.1 | 47.9 | 4.8 | 23 | <0.1 | 14.0 | 2.9 | 45 | 1.15 | 9.6 | 335.4 | 1.5 | 6 | 0.1 | 3.9 | <0.1 | 5 | <0.01 |
| 1612577 | Rock | 3.37 | 0.182 | 18.4 | 67.2 | 34.1 | 62 | 0.1 | 43.1 | 6.5 | 59 | 1.81 | 14.6 | 163.8 | 1.2 | 32 | 0.2 | 3.2 | 0.2 | 11 | 0.01 |
| 1612588 | Rock | 3.11 | 0.447 | 37.5 | 33.5 | 93.0 | 54 | 0.2 | 19.2 | 1.1 | 35 | 2.16 | 16.5 | 365.4 | 4.8 | 12 | <0.1 | 1.8 | 0.2 | 19 | 0.02 |
| 1612589 | Rock | 3.21 | 0.075 | 9.3 | 29.7 | 22.4 | 50 | 0.2 | 17.9 | 1.5 | 40 | 2.29 | 16.6 | 67.9 | 4.6 | 9 | <0.1 | 1.1 | 0.1 | 19 | 0.02 |
| 1612590 | Rock | 3.26 | 0.047 | 3.3 | 28.0 | 8.6 | 13 | 0.2 | 5.2 | 0.7 | 28 | 1.16 | 27.2 | 46.7 | 2.2 | 5 | <0.1 | 2.1 | 0.1 | 9 | 0.01 |
| 1612591 | Rock | 4.30 | 0.041 | 3.1 | 40.0 | 5.1 | 10 | 0.2 | 3.8 | 0.6 | 28 | 1.05 | 34.6 | 33.6 | 1.9 | 4 | <0.1 | 3.1 | 0.2 | 7 | <0.01 |
| 1612592 | Rock | 3.76 | 0.047 | 4.8 | 41.8 | 8.7 | 47 | 0.3 | 14.6 | 0.9 | 39 | 1.88 | 24.4 | 40.0 | 2.0 | 6 | <0.1 | 2.1 | 0.2 | 8 | <0.01 |



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BRW
Report Date: October 11, 2017

Page: 3 of 3

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000799.1

| | Method Analyte Unit MDL | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|---------|----------------------------------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | | P | La | Cr | Mg | Ba | Ti | B | Al | Na | K | W | Hg | Sc | Tl | S | Ga | Se | Te |
| | | % | ppm | ppm | % | ppm | % | ppm | % | % | % | ppm | ppm | ppm | ppm | % | ppm | ppm | ppm |
| | | 0.001 | 1 | 1 | 0.01 | 1 | 0.001 | 20 | 0.01 | 0.001 | 0.01 | 0.1 | 0.01 | 0.1 | 0.1 | 0.05 | 1 | 0.5 | 0.2 |
| 1612573 | Rock | 0.010 | 6 | 11 | 0.01 | 96 | 0.002 | <20 | 0.21 | 0.001 | 0.09 | 0.5 | 0.09 | 2.3 | <0.1 | <0.05 | <1 | 1.0 | <0.2 |
| 1612574 | Rock | 0.010 | 7 | 13 | 0.03 | 114 | 0.003 | <20 | 0.23 | <0.001 | 0.11 | 1.2 | 0.13 | 5.2 | <0.1 | <0.05 | 1 | 0.6 | <0.2 |
| 1612575 | Rock | 0.004 | 5 | 8 | 0.01 | 141 | 0.002 | <20 | 0.15 | 0.001 | 0.07 | 0.9 | 0.12 | 2.8 | <0.1 | <0.05 | <1 | <0.5 | <0.2 |
| 1612576 | Rock | 0.012 | 5 | 7 | <0.01 | 94 | 0.001 | <20 | 0.20 | <0.001 | 0.05 | 0.5 | 0.08 | 2.8 | <0.1 | <0.05 | <1 | <0.5 | <0.2 |
| 1612577 | Rock | 0.018 | 6 | 15 | <0.01 | 421 | 0.001 | <20 | 0.21 | 0.002 | 0.06 | 0.8 | 0.16 | 3.7 | <0.1 | <0.05 | <1 | 0.6 | <0.2 |
| 1612588 | Rock | 0.027 | 10 | 17 | 0.01 | 487 | 0.001 | <20 | 0.27 | 0.002 | 0.10 | 0.9 | 0.12 | 3.2 | <0.1 | <0.05 | 1 | 4.6 | <0.2 |
| 1612589 | Rock | 0.028 | 8 | 15 | 0.01 | 992 | 0.002 | <20 | 0.24 | 0.003 | 0.11 | 0.6 | 0.18 | 2.4 | <0.1 | <0.05 | 1 | 2.7 | <0.2 |
| 1612590 | Rock | 0.007 | 4 | 13 | <0.01 | 441 | 0.001 | <20 | 0.18 | 0.004 | 0.09 | 1.2 | 0.16 | 1.0 | <0.1 | <0.05 | <1 | 3.7 | 0.2 |
| 1612591 | Rock | 0.006 | 5 | 11 | <0.01 | 171 | 0.001 | <20 | 0.15 | 0.003 | 0.06 | 1.0 | 0.19 | 0.8 | <0.1 | <0.05 | <1 | 2.8 | 0.2 |
| 1612592 | Rock | 0.025 | 5 | 14 | <0.01 | 447 | 0.002 | <20 | 0.20 | 0.003 | 0.09 | 1.2 | 0.28 | 1.0 | <0.1 | <0.05 | <1 | 3.5 | <0.2 |



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

QUALITY CONTROL REPORT

WHI17000799.1

| | Method Analyte Unit MDL | WGHT | FA430 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|------------------------|----------------------------------|--------|-------|-------|-------|-------|-------|-------|-------|-------|--------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | | Wgt | Au | Mo | Cu | Pb | Zn | Ag | Ni | Co | Mn | Fe | As | Au | Th | Sr | Cd | Sb | Bi | V | Ca |
| | | kg | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | ppm | % | ppm | ppb | ppm | ppm | ppm | ppm | ppm | ppm | % |
| | | 0.01 | 0.005 | 0.1 | 0.1 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 0.1 | 1 | 0.01 | 0.5 | 0.5 | 0.1 | 1 | 0.1 | 0.1 | 0.1 | 2 |
| Pulp Duplicates | | | | | | | | | | | | | | | | | | | | | |
| 1612605 | Rock | 3.23 | 0.015 | 2.2 | 22.4 | 16.5 | 6 | 0.1 | 3.1 | 0.5 | 27 | 1.16 | 45.7 | 6.7 | 9.5 | 13 | <0.1 | 0.4 | 0.1 | 30 | 0.02 |
| REP 1612605 | QC | 0.014 | | | | | | | | | | | | | | | | | | | |
| 1612594 | Rock | 3.37 | 0.071 | 9.3 | 52.0 | 12.3 | 57 | 0.4 | 14.1 | 1.1 | 47 | 2.21 | 31.4 | 58.6 | 1.4 | 7 | <0.1 | 2.8 | 0.2 | 25 | 0.01 |
| REP 1612594 | QC | 8.5 | | 48.6 | 11.4 | 51 | 0.3 | 13.0 | 1.0 | 41 | 2.18 | 29.2 | 48.7 | 1.3 | 6 | <0.1 | 2.5 | 0.2 | 25 | 0.01 | |
| REP 1612573 | QC | 0.140 | | | | | | | | | | | | | | | | | | | |
| Core Reject Duplicates | | | | | | | | | | | | | | | | | | | | | |
| 1612573 | Rock | 3.05 | 0.134 | 5.3 | 40.5 | 16.1 | 22 | <0.1 | 16.0 | 3.0 | 41 | 1.10 | 9.8 | 101.4 | 2.0 | 9 | <0.1 | 3.5 | <0.1 | 8 | 0.01 |
| DUP 1612573 | QC | 0.137 | | 5.5 | 40.2 | 17.5 | 23 | <0.1 | 14.9 | 3.0 | 42 | 1.11 | 11.2 | 156.3 | 2.2 | 9 | <0.1 | 3.7 | <0.1 | 8 | 0.01 |
| Reference Materials | | | | | | | | | | | | | | | | | | | | | |
| STD DS11 | Standard | 14.0 | | 155.2 | 131.4 | 329 | 1.8 | 78.1 | 13.4 | 1074 | 3.18 | 41.7 | 310.2 | 7.5 | 62 | 2.4 | 6.4 | 11.4 | 50 | 1.07 | |
| STD DS11 | Standard | 13.8 | | 158.7 | 140.2 | 348 | 1.7 | 74.3 | 13.9 | 1075 | 3.07 | 42.7 | 58.2 | 7.5 | 64 | 2.4 | 5.7 | 11.6 | 44 | 1.05 | |
| STD OREAS45EA | Standard | 1.6 | | 740.9 | 13.1 | 33 | 0.3 | 393.9 | 52.0 | 422 | 23.30 | 10.6 | 46.6 | 9.7 | 4 | <0.1 | 0.2 | 0.2 | 326 | 0.03 | |
| STD OREAS45EA | Standard | 1.5 | | 737.4 | 13.3 | 33 | 0.3 | 387.7 | 51.9 | 424 | 22.79 | 10.8 | 47.6 | 9.3 | 4 | <0.1 | 0.2 | 0.2 | 319 | 0.04 | |
| STD OXC145 | Standard | 0.207 | | | | | | | | | | | | | | | | | | | |
| STD OXH139 | Standard | 1.307 | | | | | | | | | | | | | | | | | | | |
| STD OXN117 | Standard | 7.919 | | | | | | | | | | | | | | | | | | | |
| STD OXN117 Expected | | 7.679 | | | | | | | | | | | | | | | | | | | |
| STD OXC145 Expected | | 0.212 | | | | | | | | | | | | | | | | | | | |
| STD OXH139 Expected | | 1.312 | | | | | | | | | | | | | | | | | | | |
| STD OREAS45EA Expected | | 1.6 | | 709 | 14.3 | 31.4 | 0.26 | 381 | 52 | 400 | 23.51 | 10.3 | 53 | 10.7 | 3.5 | 0.03 | 0.32 | 0.26 | 303 | 0.036 | |
| STD DS11 Expected | | 13.9 | | 156 | 138 | 345 | 1.71 | 81.9 | 14.2 | 1055 | 3.2082 | 42.8 | 79 | 7.65 | 67.3 | 2.37 | 7.2 | 12.2 | 50 | 1.063 | |
| BLK | Blank | <0.005 | | | | | | | | | | | | | | | | | | | |
| BLK | Blank | <0.005 | | | | | | | | | | | | | | | | | | | |
| BLK | Blank | <0.1 | | <0.1 | <0.1 | <1 | <0.1 | <0.1 | <0.1 | <1 | <0.01 | <0.5 | <0.5 | <0.1 | <1 | <0.1 | <0.1 | <0.1 | <2 | <0.01 | |
| BLK | Blank | <0.1 | | <0.1 | 0.2 | <1 | <0.1 | <0.1 | <0.1 | <1 | <0.01 | <0.5 | <0.5 | <0.1 | <1 | <0.1 | <0.1 | <0.1 | <2 | <0.01 | |
| Prep Wash | | | | | | | | | | | | | | | | | | | | | |
| ROCK-WHI | Prep Blank | <0.005 | | 0.7 | 7.5 | 1.9 | 36 | <0.1 | 1.3 | 4.1 | 677 | 1.78 | 0.9 | <0.5 | 2.1 | 22 | <0.1 | <0.1 | <0.1 | 22 | 1.09 |
| ROCK-WHI | Prep Blank | <0.005 | | 0.9 | 4.5 | 1.2 | 38 | <0.1 | 1.3 | 4.1 | 577 | 1.86 | 1.1 | <0.5 | 2.3 | 20 | <0.1 | <0.1 | <0.1 | 22 | 0.59 |



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BRW
Report Date: October 11, 2017

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Page: 1 of 1

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17000799.1

| Method | | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 | AQ200 |
|------------------------|------------|--------|-------|-------|-------|-------|--------|-------|-------|--------|-------|-------|-------|-------|-------|--------|-------|-------|-------|
| Analyte | | P | La | Cr | Mg | Ba | Ti | B | Al | Na | K | W | Hg | Sc | Tl | S | Ga | Se | Te |
| Unit | | % | ppm | ppm | % | ppm | % | ppm | % | % | % | ppm | ppm | ppm | ppm | % | ppm | ppm | ppm |
| MDL | | 0.001 | 1 | 1 | 0.01 | 1 | 0.001 | 20 | 0.01 | 0.001 | 0.01 | 0.1 | 0.01 | 0.1 | 0.1 | 0.05 | 1 | 0.5 | 0.2 |
| Pulp Duplicates | | | | | | | | | | | | | | | | | | | |
| 1612605 | Rock | 0.014 | 21 | 20 | 0.02 | 182 | 0.001 | <20 | 0.25 | 0.004 | 0.14 | 0.2 | 0.02 | 1.8 | <0.1 | <0.05 | 1 | 0.9 | <0.2 |
| REP 1612605 | QC | | | | | | | | | | | | | | | | | | |
| 1612594 | Rock | 0.028 | 2 | 18 | 0.01 | 225 | 0.002 | <20 | 0.19 | 0.003 | 0.10 | 1.1 | 0.49 | 1.1 | <0.1 | <0.05 | <1 | 6.9 | 0.2 |
| REP 1612594 | QC | 0.026 | 2 | 15 | 0.01 | 201 | 0.002 | <20 | 0.19 | 0.002 | 0.10 | 1.1 | 0.44 | 1.0 | <0.1 | <0.05 | <1 | 5.9 | 0.2 |
| REP 1612573 | QC | | | | | | | | | | | | | | | | | | |
| Core Reject Duplicates | | | | | | | | | | | | | | | | | | | |
| 1612573 | Rock | 0.010 | 6 | 11 | 0.01 | 96 | 0.002 | <20 | 0.21 | 0.001 | 0.09 | 0.5 | 0.09 | 2.3 | <0.1 | <0.05 | <1 | 1.0 | <0.2 |
| DUP 1612573 | QC | 0.011 | 7 | 10 | 0.02 | 108 | 0.002 | <20 | 0.21 | 0.001 | 0.08 | 0.5 | 0.10 | 2.7 | <0.1 | <0.05 | <1 | 0.8 | <0.2 |
| Reference Materials | | | | | | | | | | | | | | | | | | | |
| STD DS11 | Standard | 0.070 | 17 | 62 | 0.85 | 416 | 0.098 | <20 | 1.13 | 0.070 | 0.41 | 2.7 | 0.25 | 3.3 | 4.7 | 0.29 | 5 | 2.2 | 4.5 |
| STD DS11 | Standard | 0.073 | 17 | 61 | 0.85 | 421 | 0.095 | <20 | 1.15 | 0.070 | 0.40 | 2.7 | 0.27 | 3.3 | 4.8 | 0.27 | 5 | 2.5 | 4.7 |
| STD OREAS45EA | Standard | 0.027 | 7 | 931 | 0.09 | 146 | 0.105 | <20 | 3.39 | 0.026 | 0.06 | <0.1 | 0.02 | 77.7 | <0.1 | <0.05 | 13 | 0.8 | <0.2 |
| STD OREAS45EA | Standard | 0.025 | 7 | 927 | 0.09 | 141 | 0.102 | <20 | 3.46 | 0.022 | 0.06 | <0.1 | <0.01 | 76.0 | <0.1 | <0.05 | 13 | 1.0 | <0.2 |
| STD OXC145 | Standard | | | | | | | | | | | | | | | | | | |
| STD OXH139 | Standard | | | | | | | | | | | | | | | | | | |
| STD OXN117 | Standard | | | | | | | | | | | | | | | | | | |
| STD OXN117 Expected | | | | | | | | | | | | | | | | | | | |
| STD OXC145 Expected | | | | | | | | | | | | | | | | | | | |
| STD OXH139 Expected | | | | | | | | | | | | | | | | | | | |
| STD OREAS45EA Expected | | 0.029 | 7.06 | 849 | 0.095 | 148 | 0.0984 | | 3.13 | 0.02 | 0.053 | | | 78 | 0.072 | 0.036 | 12.4 | 0.78 | 0.07 |
| STD DS11 Expected | | 0.0701 | 18.6 | 61.5 | 0.85 | 417 | 0.0976 | | 1.129 | 0.0694 | 0.4 | 2.9 | 0.3 | 3.1 | 4.9 | 0.2835 | 4.7 | 1.9 | 4.56 |
| BLK | Blank | | | | | | | | | | | | | | | | | | |
| BLK | Blank | | | | | | | | | | | | | | | | | | |
| BLK | Blank | <0.001 | <1 | <1 | <0.01 | <1 | <0.001 | <20 | <0.01 | <0.001 | <0.01 | <0.1 | <0.01 | <0.1 | <0.1 | <0.05 | <1 | <0.5 | <0.2 |
| BLK | Blank | <0.001 | <1 | <1 | <0.01 | <1 | <0.001 | <20 | <0.01 | <0.001 | <0.01 | <0.1 | <0.01 | <0.1 | <0.1 | <0.05 | <1 | <0.5 | <0.2 |
| Prep Wash | | | | | | | | | | | | | | | | | | | |
| ROCK-WHI | Prep Blank | 0.037 | 5 | 3 | 0.45 | 51 | 0.080 | <20 | 0.83 | 0.063 | 0.09 | <0.1 | <0.01 | 2.6 | <0.1 | <0.05 | 4 | <0.5 | <0.2 |
| ROCK-WHI | Prep Blank | 0.039 | 6 | 3 | 0.50 | 53 | 0.071 | <20 | 0.86 | 0.066 | 0.08 | <0.1 | <0.01 | 2.8 | <0.1 | <0.05 | 4 | <0.5 | <0.2 |