



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Submitted By: Jodie Gibson
Receiving Lab: Canada-Whitehorse
Received: June 27, 2017
Report Date: July 19, 2017
Page: 1 of 5

CERTIFICATE OF ANALYSIS

WHI17000165.1

CLIENT JOB INFORMATION

Project: DIM
Shipment ID: DIM-20170624-001-ROCK
P.O. Number
Number of Samples: 97

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.
Box 70
Dawson Yukon Y0B 1G0
Canada

CC: Isaac Fage
Shawn Ryan

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	92	Crush, split and pulverize 250 g rock to 200 mesh			WHI
SLBHP	5	Sort, label and box pulps			WHI
FA430	97	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	97	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	97	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	97	Per sample shipping charges for branch shipments			VAN
PULSW	92	Extra Wash with Silica between each sample			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 2 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method	Analyte	Unit	MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
					kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
					0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1611068	Rock				3.16	0.087	1.3	16.0	8.2	23	0.2	6.0	4.3	365	1.41	137.2	76.9	4.6	294	<0.1	0.2	<0.1	4	1.17
1611069	Rock				3.48	0.164	1.1	45.7	10.5	31	0.6	10.5	6.0	411	1.85	589.3	214.8	4.3	325	0.1	0.2	<0.1	9	1.36
1611070	Rock				4.21	0.079	1.5	21.3	5.2	35	0.2	4.9	3.9	366	1.45	935.0	77.8	2.3	202	0.1	0.3	<0.1	5	0.99
1611071	Rock				3.22	0.133	2.7	28.7	4.4	47	0.2	6.7	5.1	495	1.81	1796.6	138.7	7.9	281	0.2	0.5	<0.1	7	1.43
1611072	Rock				3.39	0.105	1.2	8.7	4.8	41	0.1	5.7	7.8	495	1.96	1059.8	110.3	6.5	508	0.1	0.3	<0.1	10	2.04
1611073	Rock				3.55	0.118	1.2	20.7	5.3	62	0.2	4.7	7.4	464	2.23	809.9	100.4	5.7	390	0.2	0.3	<0.1	17	1.94
1611074	Rock				3.17	0.710	1.3	13.0	299.3	213	1.0	3.6	4.0	329	2.09	1194.0	627.3	5.2	261	1.2	0.4	<0.1	5	1.23
1611075	Rock				3.21	0.089	1.7	14.0	8.5	33	0.2	6.7	4.9	376	1.56	1020.3	78.3	4.6	420	<0.1	0.3	<0.1	7	1.48
1611076	Rock				3.38	0.022	1.0	3.8	4.9	77	<0.1	7.1	3.3	630	1.67	64.7	10.3	4.2	1553	0.2	<0.1	<0.1	25	8.62
1611077	Rock				3.25	0.034	0.9	2.7	16.6	74	<0.1	4.5	2.5	693	1.55	16.1	8.6	2.6	1397	0.3	<0.1	<0.1	30	7.14
1611078	Rock				3.33	0.046	1.0	9.6	17.6	92	0.1	10.6	5.0	948	2.11	467.4	40.7	3.1	1489	0.3	0.2	<0.1	35	8.12
1611079	Rock				3.19	0.184	1.3	15.4	10.5	47	0.2	7.5	5.6	443	1.79	1137.3	114.1	12.4	416	0.2	0.3	<0.1	11	1.66
1611080	Rock Pulp				0.06	<0.005	2.4	23.6	2.4	43	0.3	23.6	10.1	404	2.35	5.7	46.7	0.9	41	<0.1	0.2	<0.1	58	0.84
1611081	Rock				3.49	0.163	0.7	28.5	15.0	56	0.3	23.8	13.7	585	2.88	1210.6	180.9	15.6	63	0.1	0.4	0.2	10	0.96
1611082	Rock				2.48	0.057	0.9	19.3	12.5	40	0.2	20.7	10.1	464	2.49	274.2	49.8	12.8	157	<0.1	0.2	0.2	7	1.55
1611083	Rock				2.46	0.027	0.6	20.8	11.8	58	0.2	21.5	12.8	459	3.09	221.4	22.9	13.6	285	0.1	0.2	0.1	8	1.50
1611084	Rock				2.59	0.160	0.8	30.9	13.8	64	0.4	19.6	11.5	471	2.62	1123.9	261.9	13.2	150	0.1	0.4	0.2	4	1.42
1611085	Rock				3.00	0.051	0.7	11.6	20.1	24	0.2	8.0	4.8	303	1.22	187.6	46.0	7.2	68	<0.1	0.1	0.2	3	0.96
1611086	Rock				2.65	0.173	0.8	21.8	7.4	33	0.2	18.4	10.0	480	2.63	1558.7	178.4	14.5	287	<0.1	0.4	<0.1	7	1.84
1611087	Rock				3.00	0.062	0.8	13.8	5.3	28	0.1	12.8	7.0	392	1.89	480.1	69.0	12.9	268	0.1	0.2	<0.1	5	1.66
1611088	Rock				3.03	0.047	0.7	15.0	7.0	27	0.2	18.6	9.9	522	2.30	173.4	45.2	11.8	313	<0.1	0.2	0.2	4	2.34
1611089	Rock				3.20	0.034	1.0	27.1	14.5	37	0.2	19.1	9.9	512	2.40	332.4	30.9	11.6	229	0.1	0.2	0.3	7	2.25
1611090	Rock				2.79	0.024	0.7	23.4	7.0	31	0.1	21.2	10.6	461	2.26	106.8	21.8	11.9	245	<0.1	0.2	0.1	7	1.79
1611091	Rock				3.00	0.041	0.8	18.9	7.8	31	0.2	20.0	10.5	511	2.57	231.1	37.3	13.1	214	<0.1	0.2	0.2	7	1.97
1611092	Rock				2.91	0.045	0.6	25.0	6.5	46	0.2	22.0	11.7	401	3.23	506.8	41.2	16.0	170	<0.1	0.3	<0.1	4	0.98
1611093	Rock				3.02	0.014	0.8	16.8	13.7	72	0.1	18.8	10.2	390	2.69	118.9	10.5	13.5	200	<0.1	0.2	<0.1	7	1.15
1611094	Rock				2.97	0.006	1.2	21.9	12.7	44	0.1	15.9	9.2	439	2.17	187.5	6.1	10.5	224	<0.1	0.3	0.2	9	1.63
1611095	Rock				2.88	0.006	0.9	17.9	8.9	37	0.1	17.3	9.5	404	2.40	197.9	5.7	12.8	186	<0.1	0.2	0.2	7	1.58
1611096	Rock				2.94	0.055	1.3	23.3	13.1	54	0.3	17.9	10.4	491	2.59	808.3	59.1	11.9	253	0.1	0.3	0.2	5	1.94
1611097	Rock				2.79	0.044	1.5	26.3	7.8	36	0.2	31.9	14.9	618	3.08	193.2	33.8	12.1	336	<0.1	0.3	0.1	8	2.14



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 2 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1611068	Rock				0.019	11	10	0.33	153	0.001	<20	0.25	0.037	0.26	2.5	<0.01	2.8	<0.1	0.25	<1	<0.5	<0.2
1611069	Rock				0.035	13	10	0.37	138	0.001	<20	0.32	0.036	0.28	1.2	<0.01	3.8	<0.1	0.53	1	<0.5	<0.2
1611070	Rock				0.018	8	8	0.31	171	<0.001	<20	0.25	0.059	0.18	3.1	<0.01	3.9	<0.1	0.31	<1	<0.5	<0.2
1611071	Rock				0.022	12	10	0.43	102	<0.001	<20	0.26	0.051	0.20	3.1	<0.01	5.4	<0.1	0.42	<1	<0.5	<0.2
1611072	Rock				0.018	16	7	0.64	46	<0.001	<20	0.20	0.048	0.13	3.7	<0.01	5.8	<0.1	0.42	<1	<0.5	<0.2
1611073	Rock				0.020	15	11	0.74	70	0.003	<20	0.40	0.078	0.17	3.7	<0.01	6.1	<0.1	0.49	1	<0.5	<0.2
1611074	Rock				0.015	13	7	0.42	91	<0.001	<20	0.23	0.049	0.16	5.4	0.02	3.2	<0.1	0.67	<1	<0.5	<0.2
1611075	Rock				0.024	12	11	0.45	129	0.001	<20	0.26	0.058	0.22	4.2	<0.01	4.2	<0.1	0.30	<1	<0.5	<0.2
1611076	Rock				0.025	9	13	4.60	78	<0.001	<20	0.10	0.021	0.10	2.4	<0.01	3.0	<0.1	0.06	<1	<0.5	<0.2
1611077	Rock				0.022	8	9	3.32	107	0.001	<20	0.15	0.025	0.18	0.9	<0.01	2.3	<0.1	0.07	<1	<0.5	<0.2
1611078	Rock				0.031	10	22	4.06	181	0.001	<20	0.15	0.020	0.13	1.4	0.01	4.0	<0.1	0.26	<1	<0.5	<0.2
1611079	Rock				0.021	16	10	0.55	119	<0.001	<20	0.25	0.052	0.20	3.7	<0.01	4.9	<0.1	0.35	<1	<0.5	<0.2
1611080	Rock Pulp				0.055	4	31	0.77	93	0.140	<20	1.60	0.079	0.13	12.2	0.01	4.8	<0.1	<0.05	5	<0.5	<0.2
1611081	Rock				0.032	37	10	0.11	197	0.007	<20	0.52	0.017	0.28	1.3	0.01	3.5	<0.1	<0.05	1	<0.5	<0.2
1611082	Rock				0.028	31	10	0.16	138	0.002	<20	0.42	0.025	0.26	0.8	<0.01	3.3	<0.1	0.05	1	<0.5	<0.2
1611083	Rock				0.024	35	6	0.52	154	0.002	<20	0.35	0.015	0.27	0.4	<0.01	4.5	<0.1	0.09	<1	<0.5	<0.2
1611084	Rock				0.024	38	8	0.19	305	0.001	<20	0.36	0.006	0.29	1.1	<0.01	2.6	<0.1	0.07	<1	<0.5	<0.2
1611085	Rock				0.016	21	5	0.11	41	<0.001	<20	0.25	0.004	0.19	2.3	<0.01	1.2	<0.1	0.05	<1	<0.5	<0.2
1611086	Rock				0.029	32	9	0.45	249	0.001	<20	0.71	0.009	0.31	0.5	<0.01	3.2	<0.1	0.09	2	<0.5	<0.2
1611087	Rock				0.020	30	9	0.41	109	0.002	<20	0.41	0.022	0.30	1.1	<0.01	2.0	<0.1	0.10	1	<0.5	<0.2
1611088	Rock				0.025	27	8	0.46	167	0.001	<20	0.33	0.016	0.28	1.2	<0.01	2.3	0.1	0.20	<1	<0.5	<0.2
1611089	Rock				0.042	29	12	0.57	170	0.002	<20	0.53	0.022	0.37	1.1	<0.01	2.9	0.1	0.24	2	<0.5	<0.2
1611090	Rock				0.030	30	10	0.53	190	0.002	<20	0.47	0.027	0.24	0.9	<0.01	3.4	<0.1	0.15	2	<0.5	<0.2
1611091	Rock				0.028	32	11	0.65	237	0.001	<20	0.60	0.025	0.33	0.6	<0.01	3.2	0.1	0.13	2	<0.5	<0.2
1611092	Rock				0.028	44	8	0.34	98	0.002	<20	0.49	0.015	0.30	0.7	<0.01	2.3	<0.1	0.07	1	<0.5	<0.2
1611093	Rock				0.022	35	11	0.55	115	0.002	<20	0.78	0.026	0.28	0.7	<0.01	2.8	<0.1	<0.05	2	<0.5	<0.2
1611094	Rock				0.023	29	11	0.53	47	0.006	<20	0.55	0.018	0.24	1.4	<0.01	2.6	<0.1	0.14	2	<0.5	<0.2
1611095	Rock				0.024	34	12	0.57	34	0.002	<20	0.69	0.019	0.31	0.5	<0.01	2.5	<0.1	0.09	2	<0.5	<0.2
1611096	Rock				0.023	30	10	0.61	60	0.002	<20	0.48	0.014	0.31	1.2	<0.01	2.4	<0.1	0.22	1	<0.5	<0.2
1611097	Rock				0.035	32	14	0.84	140	0.002	<20	0.72	0.007	0.39	0.4	<0.01	4.3	0.1	0.08	2	<0.5	<0.2



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 3 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1611098	Rock	2.41	0.117	1.2	22.2	9.0	55	0.3	19.7	10.3	593	2.42	639.0	108.6	10.9	376	0.2	0.2	0.1	6	1.76
1611099	Rock	2.56	0.082	1.2	36.9	4.0	18	0.3	7.5	3.8	272	1.16	365.3	70.1	7.1	205	<0.1	0.3	<0.1	4	0.79
1611100	Rock Pulp	0.08	5.355	7.6	196.3	23.1	75	0.7	14.6	11.3	574	4.29	11.9	3933.1	3.1	77	0.2	4.0	0.5	102	0.99
1611101	Rock	2.98	0.060	1.5	20.9	8.2	51	0.2	23.2	10.4	643	2.35	240.2	62.2	8.9	739	0.2	0.2	0.2	10	2.52
1611102	Rock	2.99	0.069	1.9	41.2	25.9	102	0.3	23.1	11.7	730	2.80	251.8	66.4	11.2	844	0.5	0.7	0.3	13	3.12
1611103	Rock	2.27	0.022	1.2	12.6	10.0	31	0.2	6.7	3.2	333	1.11	96.7	23.1	8.6	263	0.1	0.1	<0.1	3	1.26
1611104	Rock	2.68	0.037	2.6	26.6	33.3	97	0.4	24.0	11.4	802	2.86	318.0	25.1	10.3	685	0.5	0.3	0.2	19	4.20
1611105	Rock	3.42	0.030	1.3	16.4	11.5	60	0.2	20.0	10.4	720	2.60	231.6	21.8	8.9	540	0.2	0.2	0.1	11	3.25
1611106	Rock	3.22	0.010	1.8	12.9	6.7	38	0.1	12.0	5.2	426	1.61	36.3	7.6	8.7	350	<0.1	0.1	<0.1	7	1.87
1611107	Rock	3.10	0.016	1.1	15.8	1.8	15	<0.1	3.7	2.0	192	0.68	48.8	27.3	5.6	165	<0.1	0.1	<0.1	<2	0.59
1611108	Rock	2.67	0.065	1.4	27.7	3.1	23	0.4	7.7	5.2	348	1.45	286.8	39.8	6.2	328	<0.1	0.2	<0.1	6	1.32
1611109	Rock	3.14	0.278	1.3	29.5	6.9	42	0.5	14.5	9.0	728	2.77	2666.6	278.8	5.2	708	0.2	0.6	<0.1	12	2.94
1611110	Rock	3.01	0.346	1.1	26.2	5.5	45	0.4	6.6	8.4	654	2.51	3439.5	319.9	2.8	585	0.3	0.8	<0.1	15	2.39
1611111	Rock	2.94	0.989	1.4	33.1	15.3	50	0.9	8.0	15.7	1087	4.55	6505.9	1009.2	1.4	897	0.1	1.2	<0.1	21	3.68
1611112	Rock	3.55	0.317	3.3	20.9	8.5	42	0.3	7.9	8.8	553	2.46	1830.7	293.6	5.2	439	0.1	0.6	<0.1	11	1.69
1611113	Rock	3.04	0.201	1.4	9.6	34.7	40	0.3	7.1	6.4	513	2.15	1724.3	197.4	5.6	537	0.2	0.5	<0.1	10	1.80
1611114	Rock	2.99	0.175	1.5	18.8	14.4	103	0.5	13.5	15.2	839	3.39	2167.2	179.7	2.7	522	0.4	0.7	<0.1	36	2.73
1611115	Rock	3.21	0.098	1.3	13.8	61.8	109	0.5	10.8	11.5	956	3.28	1521.5	88.5	2.2	492	0.8	0.5	<0.1	20	3.36
1611116	Rock	3.19	0.228	1.1	4.4	76.8	125	0.6	13.2	8.2	1833	4.75	1074.9	211.0	4.1	757	0.5	0.3	<0.1	20	6.11
1611117	Rock	3.13	0.049	1.4	6.8	29.4	82	0.2	6.5	3.5	637	1.91	59.4	32.9	14.5	344	0.2	0.1	<0.1	8	2.09
1611118	Rock	3.21	0.060	1.3	10.8	5.4	55	0.2	10.8	7.6	765	2.43	477.0	55.9	5.5	619	0.2	0.3	<0.1	14	2.90
1611119	Rock	3.24	0.057	1.2	31.0	9.7	97	0.3	61.5	16.7	1035	3.38	412.3	54.6	4.9	802	0.3	0.5	<0.1	44	4.16
1611120	Rock Pulp	0.06	0.008	2.4	24.8	2.3	43	0.3	23.6	10.5	406	2.40	5.1	<0.5	0.9	42	0.2	0.3	<0.1	59	0.83
1611121	Rock	2.92	0.062	1.4	22.4	5.6	56	0.2	11.6	8.3	666	2.45	501.3	65.7	2.8	604	0.2	0.4	<0.1	23	2.33
1611122	Rock	3.05	0.303	1.4	130.4	31.8	127	1.4	14.4	19.0	965	4.65	1813.3	303.0	3.9	799	0.6	0.6	0.4	28	3.51
1611123	Rock	2.98	0.129	1.5	69.9	12.4	90	0.6	9.6	12.1	744	2.84	1006.0	149.9	2.9	702	0.6	0.4	<0.1	19	2.92
1611124	Rock	3.11	0.214	1.3	26.5	7.4	71	0.4	6.4	9.4	634	2.70	1434.3	172.8	3.6	480	0.3	0.4	<0.1	15	2.90
1611125	Rock	3.02	0.010	0.2	43.3	6.2	105	<0.1	51.9	34.9	1083	6.35	34.3	61.5	1.0	324	0.2	0.2	0.1	133	4.29
1611126	Rock	2.86	0.007	0.2	38.3	6.0	92	<0.1	48.8	31.9	958	6.14	49.4	4.9	0.7	345	0.1	0.2	<0.1	116	5.10
1611127	Rock	3.02	<0.005	0.2	33.6	4.1	96	<0.1	46.9	33.3	1268	6.86	55.3	2.4	0.8	412	0.2	0.2	<0.1	129	4.35



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 3 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1611098	Rock				0.022	26	9	0.55	169	<0.001	<20	0.54	0.009	0.19	0.9	<0.01	3.8	<0.1	0.08	1	<0.5	<0.2
1611099	Rock				0.012	20	9	0.25	137	<0.001	<20	0.26	0.043	0.20	1.9	<0.01	2.0	<0.1	0.07	<1	<0.5	<0.2
1611100	Rock Pulp				0.054	8	19	0.88	129	0.157	<20	1.84	0.198	0.23	5.3	0.14	3.4	<0.1	<0.05	5	<0.5	<0.2
1611101	Rock				0.041	24	9	0.80	162	<0.001	<20	0.25	0.016	0.20	1.8	<0.01	4.6	<0.1	0.19	1	<0.5	<0.2
1611102	Rock				0.064	29	12	1.00	143	0.002	<20	0.50	0.018	0.38	1.3	<0.01	4.6	0.1	0.51	2	<0.5	<0.2
1611103	Rock				0.020	16	7	0.28	628	<0.001	<20	0.23	0.020	0.15	1.6	<0.01	1.4	<0.1	0.08	<1	<0.5	<0.2
1611104	Rock				0.037	27	17	1.29	220	0.001	<20	0.51	0.019	0.28	0.9	0.01	5.3	<0.1	0.32	2	<0.5	<0.2
1611105	Rock				0.032	24	14	0.97	135	0.001	<20	0.26	0.025	0.24	2.3	<0.01	5.8	<0.1	0.39	<1	<0.5	<0.2
1611106	Rock				0.022	20	12	0.55	64	0.001	<20	0.23	0.050	0.21	3.7	<0.01	3.2	<0.1	0.10	<1	<0.5	<0.2
1611107	Rock				0.008	12	7	0.13	73	<0.001	<20	0.17	0.048	0.18	4.1	<0.01	0.9	<0.1	<0.05	<1	<0.5	<0.2
1611108	Rock				0.012	11	10	0.42	132	0.001	<20	0.26	0.060	0.23	4.1	<0.01	3.6	<0.1	0.27	1	<0.5	<0.2
1611109	Rock				0.051	14	12	0.93	154	0.001	<20	0.24	0.034	0.19	2.4	<0.01	8.1	<0.1	0.69	<1	<0.5	<0.2
1611110	Rock				0.030	10	9	0.79	133	0.002	<20	0.31	0.038	0.24	3.6	<0.01	7.6	0.1	0.58	1	<0.5	<0.2
1611111	Rock				0.040	5	8	1.16	173	0.002	<20	0.32	0.031	0.23	2.5	<0.01	14.7	<0.1	1.76	1	<0.5	<0.2
1611112	Rock				0.045	12	10	0.54	107	0.002	<20	0.33	0.062	0.22	5.2	<0.01	7.9	<0.1	1.06	1	<0.5	<0.2
1611113	Rock				0.026	11	9	0.56	216	<0.001	<20	0.25	0.043	0.19	2.7	<0.01	5.7	<0.1	0.59	<1	<0.5	<0.2
1611114	Rock				0.023	7	11	1.05	116	0.009	<20	0.73	0.051	0.31	1.5	<0.01	14.6	0.1	0.61	3	<0.5	<0.2
1611115	Rock				0.020	7	8	1.10	334	0.002	<20	0.45	0.031	0.19	1.2	<0.01	14.0	<0.1	0.29	2	<0.5	<0.2
1611116	Rock				0.032	8	11	1.87	1634	<0.001	<20	0.45	0.020	0.25	0.7	0.02	6.1	<0.1	0.27	2	<0.5	<0.2
1611117	Rock				0.016	21	9	0.59	1687	<0.001	<20	0.20	0.043	0.15	2.3	<0.01	2.7	<0.1	0.21	<1	<0.5	<0.2
1611118	Rock				0.052	19	13	0.86	394	0.002	<20	0.27	0.040	0.21	1.8	<0.01	6.9	<0.1	0.25	<1	<0.5	<0.2
1611119	Rock				0.069	19	49	1.52	437	0.009	<20	0.61	0.022	0.26	2.1	0.01	8.4	<0.1	0.54	2	<0.5	<0.2
1611120	Rock Pulp				0.056	4	31	0.78	97	0.139	<20	1.60	0.082	0.13	13.5	<0.01	4.8	<0.1	<0.05	5	<0.5	<0.2
1611121	Rock				0.036	12	18	0.87	230	0.006	<20	0.43	0.035	0.31	3.0	<0.01	7.0	<0.1	0.44	2	<0.5	<0.2
1611122	Rock				0.048	9	27	1.44	136	0.004	<20	0.50	0.055	0.29	2.2	<0.01	12.2	0.1	1.41	2	2.7	<0.2
1611123	Rock				0.037	8	13	1.04	186	0.002	<20	0.29	0.046	0.19	2.5	<0.01	10.0	<0.1	0.83	1	0.8	<0.2
1611124	Rock				0.039	12	10	0.93	203	0.001	<20	0.27	0.080	0.15	3.8	<0.01	9.6	<0.1	0.58	<1	<0.5	<0.2
1611125	Rock				0.154	17	70	2.67	594	0.143	<20	4.94	0.048	0.08	<0.1	0.02	16.6	0.1	<0.05	11	<0.5	<0.2
1611126	Rock				0.127	14	70	2.78	192	0.052	<20	4.71	0.009	0.08	<0.1	0.02	15.3	<0.1	<0.05	11	<0.5	<0.2
1611127	Rock				0.145	16	62	3.00	227	0.076	<20	4.08	0.042	0.08	<0.1	0.02	14.2	<0.1	<0.05	10	<0.5	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 4 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1611128	Rock	3.77	<0.005	0.5	31.4	3.6	112	<0.1	41.2	35.5	830	5.90	16.3	0.8	1.2	381	0.2	0.2	<0.1	138	3.54
1611129	Rock	3.11	<0.005	0.4	35.7	3.1	112	<0.1	42.0	33.6	740	5.72	16.4	1.2	1.0	324	0.1	0.2	<0.1	124	3.43
1611130	Rock	3.29	<0.005	0.5	30.4	3.2	95	<0.1	41.2	31.3	647	5.52	13.2	0.6	1.0	320	0.1	0.1	<0.1	119	3.46
1611131	Rock	3.05	0.006	0.6	28.8	2.8	95	<0.1	42.9	33.6	708	6.06	16.4	1.4	1.2	269	0.1	<0.1	<0.1	135	3.38
1611132	Rock	3.20	<0.005	0.3	29.0	3.3	90	<0.1	46.3	32.6	727	5.90	11.6	<0.5	1.1	375	0.2	0.1	<0.1	127	4.01
1611133	Rock	3.06	<0.005	0.5	25.3	3.1	93	<0.1	45.0	34.4	865	5.77	13.3	1.4	1.0	382	0.1	0.1	<0.1	117	3.67
1611134	Rock	3.38	<0.005	0.4	28.0	3.3	102	<0.1	47.5	34.1	823	5.93	14.2	<0.5	1.0	310	0.1	0.1	<0.1	111	3.66
1611135	Rock	2.78	<0.005	0.4	28.5	3.1	108	<0.1	42.1	33.2	636	5.90	20.7	1.9	1.1	289	0.1	0.1	<0.1	120	3.39
1611136	Rock	3.25	<0.005	0.5	32.0	4.0	126	<0.1	40.8	34.3	681	5.63	37.3	6.2	1.1	261	<0.1	0.2	<0.1	125	3.12
1611137	Rock	2.84	<0.005	0.4	27.9	2.8	97	<0.1	41.0	32.7	840	5.90	54.5	3.1	1.1	245	<0.1	0.2	<0.1	131	3.28
1611138	Rock	3.23	<0.005	0.6	28.6	2.7	100	<0.1	46.0	35.9	843	6.99	12.5	2.3	1.2	491	<0.1	0.1	<0.1	164	4.68
1611139	Rock	2.96	<0.005	0.9	28.7	3.7	112	<0.1	44.5	39.2	1407	5.79	13.5	1.0	1.2	663	0.1	0.2	<0.1	153	4.11
1611140	Rock Pulp	0.08	0.441	6.2	272.0	14.3	49	0.6	108.6	14.6	459	2.79	167.8	298.9	3.2	77	0.2	1.7	0.2	64	1.80
1611141	Rock	3.12	<0.005	0.7	27.3	2.7	108	<0.1	42.9	36.0	853	5.96	33.5	3.0	1.2	265	0.2	<0.1	<0.1	151	3.36
1611142	Rock	3.39	<0.005	0.7	27.7	2.2	87	<0.1	42.5	31.9	694	6.00	14.3	<0.5	1.1	403	0.2	0.2	<0.1	143	3.89
1611143	Rock	2.98	<0.005	0.7	25.1	1.9	88	<0.1	38.6	29.8	780	5.61	10.2	0.7	1.1	516	<0.1	0.2	<0.1	122	4.13
1611144	Rock	2.74	<0.005	0.7	24.9	2.1	96	<0.1	39.4	30.6	836	6.17	11.0	<0.5	1.2	584	0.1	0.3	<0.1	118	4.21
1611145	Rock	3.95	<0.005	0.9	25.8	2.7	102	<0.1	41.3	33.4	812	5.45	19.0	<0.5	1.1	559	0.1	0.4	<0.1	114	3.93
1611146	Rock	3.56	<0.005	0.8	33.1	3.2	104	<0.1	44.7	33.6	702	5.31	15.4	<0.5	1.1	541	0.1	0.3	<0.1	111	4.03
1611147	Rock	3.04	<0.005	0.4	30.9	1.3	76	<0.1	58.2	30.8	1313	5.92	21.0	<0.5	0.6	588	0.2	0.2	<0.1	113	4.67
1611148	Rock	3.44	<0.005	0.6	34.4	2.0	92	<0.1	65.5	37.3	952	5.23	10.3	<0.5	0.8	677	0.1	0.2	<0.1	123	4.30
1611149	Rock	4.15	<0.005	0.6	28.9	2.1	62	<0.1	43.8	23.3	690	3.87	21.8	1.6	3.8	457	0.1	0.4	<0.1	76	3.18
1611150	Rock	3.94	<0.005	0.7	33.3	3.0	75	<0.1	48.7	27.6	911	4.44	14.6	<0.5	2.1	837	<0.1	0.3	<0.1	95	4.58
1611151	Rock	3.24	<0.005	0.4	34.3	2.6	80	<0.1	63.3	38.6	929	5.49	24.1	1.0	0.9	682	0.1	0.3	<0.1	116	5.18
1611152	Rock	4.30	<0.005	0.6	34.8	2.1	92	<0.1	63.6	33.7	1175	4.86	8.9	<0.5	0.9	1215	<0.1	0.4	<0.1	112	5.21
1611153	Rock	3.66	0.025	0.5	26.9	3.3	86	0.1	50.7	28.1	735	5.35	77.3	31.9	2.2	526	0.2	0.5	<0.1	78	3.66
1611154	Rock	3.59	0.015	0.8	32.9	3.3	56	0.2	7.6	8.4	687	2.74	108.7	12.8	6.6	101	0.2	0.4	<0.1	20	2.01
1611155	Rock	3.71	0.043	0.9	10.2	2.7	25	0.2	5.9	5.4	341	1.81	281.2	39.9	9.0	62	<0.1	0.3	<0.1	11	0.79
1611156	Rock	3.63	0.012	0.9	13.4	2.4	37	0.1	5.6	4.8	387	1.86	64.3	12.0	10.4	66	<0.1	0.2	<0.1	11	1.67
1611157	Rock	4.41	0.140	0.7	16.1	4.2	49	0.3	9.1	16.6	832	3.85	1804.7	133.8	3.3	438	0.1	0.7	<0.1	26	4.02



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 4 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1611128	Rock				0.201	20	54	2.29	199	0.341	<20	3.19	0.220	0.11	<0.1	0.01	13.2	<0.1	<0.05	8	<0.5	<0.2
1611129	Rock				0.182	19	53	2.22	122	0.325	<20	3.12	0.244	0.11	<0.1	<0.01	8.7	<0.1	<0.05	8	<0.5	<0.2
1611130	Rock				0.176	19	50	2.42	97	0.358	<20	3.35	0.268	0.10	<0.1	<0.01	9.9	<0.1	<0.05	8	<0.5	<0.2
1611131	Rock				0.175	18	54	2.89	138	0.365	<20	3.88	0.236	0.10	<0.1	<0.01	14.6	<0.1	<0.05	9	<0.5	<0.2
1611132	Rock				0.172	19	51	2.93	108	0.366	<20	3.79	0.231	0.10	<0.1	<0.01	14.4	<0.1	<0.05	9	<0.5	<0.2
1611133	Rock				0.160	17	50	2.78	136	0.333	<20	3.57	0.265	0.10	<0.1	<0.01	11.9	<0.1	<0.05	8	<0.5	<0.2
1611134	Rock				0.168	19	53	2.64	178	0.319	<20	3.74	0.253	0.10	<0.1	<0.01	11.0	<0.1	<0.05	8	<0.5	<0.2
1611135	Rock				0.165	18	53	2.51	218	0.356	<20	3.74	0.297	0.10	<0.1	<0.01	12.0	<0.1	<0.05	8	<0.5	<0.2
1611136	Rock				0.186	19	53	2.30	128	0.361	<20	3.38	0.272	0.11	<0.1	0.02	12.2	<0.1	<0.05	8	<0.5	<0.2
1611137	Rock				0.192	18	51	2.55	103	0.279	<20	3.61	0.229	0.10	<0.1	0.01	13.8	<0.1	<0.05	8	<0.5	<0.2
1611138	Rock				0.190	19	56	2.93	137	0.258	<20	3.75	0.242	0.11	<0.1	0.03	16.5	<0.1	<0.05	9	<0.5	<0.2
1611139	Rock				0.195	20	54	2.49	129	0.275	<20	3.42	0.321	0.11	<0.1	0.02	19.7	0.2	<0.05	9	<0.5	<0.2
1611140	Rock Pulp				0.032	9	108	1.42	123	0.101	<20	2.68	0.315	0.22	1.0	0.04	2.8	0.1	0.09	6	<0.5	<0.2
1611141	Rock				0.205	20	54	2.79	106	0.294	<20	3.53	0.219	0.10	<0.1	0.02	17.0	0.1	<0.05	9	0.5	<0.2
1611142	Rock				0.185	17	51	2.80	268	0.198	<20	3.30	0.215	0.10	<0.1	0.01	13.6	<0.1	<0.05	8	<0.5	<0.2
1611143	Rock				0.183	18	49	2.34	88	0.244	<20	3.05	0.280	0.11	<0.1	0.01	11.6	<0.1	<0.05	8	<0.5	<0.2
1611144	Rock				0.175	17	47	2.51	125	0.229	<20	3.05	0.239	0.09	<0.1	<0.01	14.2	<0.1	<0.05	8	<0.5	<0.2
1611145	Rock				0.191	18	49	2.02	140	0.257	<20	2.97	0.340	0.11	<0.1	0.01	10.9	0.1	<0.05	7	<0.5	<0.2
1611146	Rock				0.188	18	57	1.94	77	0.248	<20	3.32	0.404	0.12	<0.1	0.02	11.2	0.2	0.05	8	<0.5	<0.2
1611147	Rock				0.127	13	74	2.86	102	0.116	<20	3.91	0.311	0.09	<0.1	<0.01	15.5	0.1	<0.05	8	<0.5	<0.2
1611148	Rock				0.128	14	82	2.71	114	0.182	<20	4.03	0.503	0.15	<0.1	<0.01	17.1	0.1	<0.05	8	<0.5	<0.2
1611149	Rock				0.099	17	56	1.68	121	0.176	<20	2.79	0.415	0.14	0.2	0.03	7.3	0.1	0.07	6	<0.5	<0.2
1611150	Rock				0.108	13	62	1.93	288	0.165	<20	3.31	0.380	0.16	<0.1	0.02	11.6	0.1	<0.05	7	<0.5	<0.2
1611151	Rock				0.141	15	76	2.28	197	0.019	<20	3.69	0.089	0.18	<0.1	0.06	16.6	0.1	<0.05	9	<0.5	<0.2
1611152	Rock				0.123	13	76	2.16	128	0.167	<20	3.72	0.476	0.13	<0.1	0.04	16.7	0.1	0.05	8	<0.5	<0.2
1611153	Rock				0.098	15	48	2.44	240	0.018	<20	3.05	0.052	0.27	<0.1	0.04	15.8	<0.1	0.09	7	<0.5	<0.2
1611154	Rock				0.047	22	10	0.35	236	0.011	<20	0.88	0.078	0.23	0.3	<0.01	9.9	<0.1	<0.05	3	<0.5	<0.2
1611155	Rock				0.038	27	9	0.18	94	0.014	<20	0.60	0.109	0.18	0.5	<0.01	5.6	<0.1	<0.05	2	<0.5	<0.2
1611156	Rock				0.028	29	10	0.17	80	0.014	<20	0.54	0.095	0.17	0.5	<0.01	5.8	<0.1	<0.05	1	<0.5	<0.2
1611157	Rock				0.045	12	9	0.99	77	0.006	<20	0.76	0.050	0.40	0.5	<0.01	12.6	0.1	0.28	2	<0.5	<0.2



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 5 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1611158	Rock	3.52	0.043	0.9	11.0	3.2	40	0.2	9.8	11.6	685	2.91	246.4	38.6	7.0	181	0.1	0.3	<0.1	18	3.74
1611159	Rock	3.74	0.012	2.6	14.5	2.6	28	0.1	6.3	7.3	554	2.35	58.8	10.5	7.8	352	0.2	0.2	<0.1	15	2.77
1611160	Rock Pulp	0.07	<0.005	2.4	24.6	2.2	42	0.4	22.9	9.9	389	2.32	4.7	<0.5	0.9	39	0.2	0.3	<0.1	59	0.85
1611161	Rock	3.33	0.013	3.7	14.4	3.8	40	0.2	7.3	10.4	1310	4.30	47.7	11.4	4.9	582	0.2	0.2	<0.1	22	5.46
1611162	Rock	3.64	0.020	1.2	17.3	2.9	23	0.2	7.4	8.1	721	2.63	54.2	16.9	9.4	466	<0.1	0.2	<0.1	18	2.69
1611163	Rock	4.11	0.018	1.0	25.7	3.0	20	0.2	5.6	8.0	726	2.77	23.9	17.9	8.1	734	<0.1	0.3	<0.1	25	2.71
1611164	Rock	3.51	0.021	0.9	36.8	2.5	18	0.3	5.9	7.9	720	2.68	21.6	16.3	7.0	779	<0.1	0.2	<0.1	31	3.18



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 5 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17000165.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1611158	Rock	0.040	23	9	0.41	138	0.005	<20	0.77	0.068	0.28	0.6	<0.01	9.6	<0.1	<0.05	2	<0.5	<0.2
1611159	Rock	0.036	30	10	0.79	52	0.014	<20	0.51	0.094	0.22	2.1	<0.01	8.8	<0.1	0.15	2	<0.5	<0.2
1611160	Rock Pulp	0.054	4	31	0.76	93	0.130	<20	1.56	0.081	0.13	13.7	<0.01	4.8	<0.1	<0.05	5	<0.5	<0.2
1611161	Rock	0.036	13	9	1.23	123	0.010	<20	0.45	0.047	0.22	0.6	<0.01	8.6	<0.1	0.13	1	<0.5	<0.2
1611162	Rock	0.037	22	10	0.60	172	0.013	<20	0.53	0.071	0.23	0.8	<0.01	6.4	<0.1	0.05	2	<0.5	<0.2
1611163	Rock	0.047	23	9	0.86	86	0.015	<20	0.48	0.127	0.19	0.6	<0.01	9.0	<0.1	0.16	2	<0.5	<0.2
1611164	Rock	0.078	16	9	0.95	59	0.012	<20	0.52	0.130	0.14	0.6	<0.01	9.2	<0.1	0.11	2	<0.5	<0.2



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

DIM

Report Date:

July 19, 2017

Page:

1 of 2

Part:

1 of 2

QUALITY CONTROL REPORT

WHI17000165.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
Pulp Duplicates																					
1611077	Rock	3.25	0.034	0.9	2.7	16.6	74	<0.1	4.5	2.5	693	1.55	16.1	8.6	2.6	1397	0.3	<0.1	<0.1	30	7.14
REP 1611077	QC			0.8	1.9	16.5	69	<0.1	4.5	2.6	688	1.54	16.0	4.8	3.1	1406	0.3	0.1	<0.1	30	7.08
1611078	Rock	3.33	0.046	1.0	9.6	17.6	92	0.1	10.6	5.0	948	2.11	467.4	40.7	3.1	1489	0.3	0.2	<0.1	35	8.12
REP 1611078	QC		0.046																		
1611109	Rock	3.14	0.278	1.3	29.5	6.9	42	0.5	14.5	9.0	728	2.77	2666.6	278.8	5.2	708	0.2	0.6	<0.1	12	2.94
REP 1611109	QC		0.284																		
1611110	Rock	3.01	0.346	1.1	26.2	5.5	45	0.4	6.6	8.4	654	2.51	3439.5	319.9	2.8	585	0.3	0.8	<0.1	15	2.39
REP 1611110	QC			1.3	26.2	5.5	45	0.4	6.7	8.8	653	2.52	3450.0	362.5	3.0	580	0.3	0.8	<0.1	15	2.38
1611144	Rock	2.74	<0.005	0.7	24.9	2.1	96	<0.1	39.4	30.6	836	6.17	11.0	<0.5	1.2	584	0.1	0.3	<0.1	118	4.21
REP 1611144	QC			0.7	24.6	2.1	91	<0.1	38.7	30.3	851	6.19	11.1	<0.5	1.0	582	<0.1	0.3	<0.1	119	4.20
1611151	Rock	3.24	<0.005	0.4	34.3	2.6	80	<0.1	63.3	38.6	929	5.49	24.1	1.0	0.9	682	0.1	0.3	<0.1	116	5.18
REP 1611151	QC		<0.005																		
Core Reject Duplicates																					
1611085	Rock	3.00	0.051	0.7	11.6	20.1	24	0.2	8.0	4.8	303	1.22	187.6	46.0	7.2	68	<0.1	0.1	0.2	3	0.96
DUP 1611085	QC		0.052	0.8	11.2	21.9	24	0.2	9.0	4.9	320	1.23	196.0	57.2	8.0	74	<0.1	0.1	0.2	3	0.98
1611119	Rock	3.24	0.057	1.2	31.0	9.7	97	0.3	61.5	16.7	1035	3.38	412.3	54.6	4.9	802	0.3	0.5	<0.1	44	4.16
DUP 1611119	QC		0.059	1.1	34.2	9.7	100	0.3	62.0	16.5	1047	3.39	428.2	65.8	4.9	786	0.3	0.5	<0.1	44	4.14
1611153	Rock	3.66	0.025	0.5	26.9	3.3	86	0.1	50.7	28.1	735	5.35	77.3	31.9	2.2	526	0.2	0.5	<0.1	78	3.66
DUP 1611153	QC		0.026	0.4	26.5	3.3	80	0.1	50.9	29.0	747	5.41	76.9	24.0	2.2	550	<0.1	0.5	<0.1	79	3.76
Reference Materials																					
STD DS10	Standard			13.9	151.9	148.0	356	1.9	74.6	12.9	872	2.72	44.7	86.2	7.7	67	2.5	8.2	11.9	42	1.06
STD DS10	Standard			14.2	153.8	152.5	357	1.9	75.7	12.7	865	2.73	45.4	77.7	7.8	70	2.5	8.7	12.0	43	1.03
STD DS10	Standard			13.7	154.5	155.3	363	1.7	75.1	12.9	898	2.76	42.6	57.3	7.5	72	2.5	7.2	12.7	43	1.08
STD OREAS45EA	Standard			1.8	707.0	14.1	31	0.2	402.2	53.2	404	21.81	12.0	54.7	9.7	4	<0.1	0.3	0.2	317	0.03
STD OREAS45EA	Standard			1.5	711.5	14.0	31	0.3	385.3	52.3	401	22.10	10.9	59.6	10.0	5	<0.1	0.3	0.3	304	0.04
STD OREAS45EA	Standard			1.4	723.6	13.5	32	0.2	391.2	53.4	410	22.97	12.3	52.8	9.5	4	<0.1	0.3	0.2	307	0.04
STD OXC145	Standard		0.210																		
STD OXC145	Standard		0.209																		



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17000165.1

		Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																				
1611077	Rock		0.022	8	9	3.32	107	0.001	<20	0.15	0.025	0.18	0.9	<0.01	2.3	<0.1	0.07	<1	<0.5	<0.2
REP 1611077	QC		0.023	8	9	3.32	108	0.001	<20	0.15	0.024	0.17	1.0	<0.01	2.3	<0.1	0.07	<1	<0.5	<0.2
1611078	Rock		0.031	10	22	4.06	181	0.001	<20	0.15	0.020	0.13	1.4	0.01	4.0	<0.1	0.26	<1	<0.5	<0.2
REP 1611078	QC																			
1611109	Rock		0.051	14	12	0.93	154	0.001	<20	0.24	0.034	0.19	2.4	<0.01	8.1	<0.1	0.69	<1	<0.5	<0.2
REP 1611109	QC																			
1611110	Rock		0.030	10	9	0.79	133	0.002	<20	0.31	0.038	0.24	3.6	<0.01	7.6	0.1	0.58	1	<0.5	<0.2
REP 1611110	QC		0.030	10	9	0.79	130	0.002	<20	0.31	0.038	0.24	3.6	<0.01	8.0	<0.1	0.58	1	<0.5	<0.2
1611144	Rock		0.175	17	47	2.51	125	0.229	<20	3.05	0.239	0.09	<0.1	<0.01	14.2	<0.1	<0.05	8	<0.5	<0.2
REP 1611144	QC		0.168	17	46	2.52	123	0.225	<20	3.07	0.232	0.09	<0.1	<0.01	13.8	0.1	<0.05	8	<0.5	<0.2
1611151	Rock		0.141	15	76	2.28	197	0.019	<20	3.69	0.089	0.18	<0.1	0.06	16.6	0.1	<0.05	9	<0.5	<0.2
REP 1611151	QC																			
Core Reject Duplicates																				
1611085	Rock		0.016	21	5	0.11	41	<0.001	<20	0.25	0.004	0.19	2.3	<0.01	1.2	<0.1	0.05	<1	<0.5	<0.2
DUP 1611085	QC		0.018	22	5	0.12	46	<0.001	<20	0.26	0.004	0.19	2.3	<0.01	1.4	<0.1	0.05	<1	<0.5	<0.2
1611119	Rock		0.069	19	49	1.52	437	0.009	<20	0.61	0.022	0.26	2.1	0.01	8.4	<0.1	0.54	2	<0.5	<0.2
DUP 1611119	QC		0.067	18	50	1.53	417	0.009	<20	0.62	0.022	0.26	1.9	<0.01	8.6	0.1	0.54	2	<0.5	<0.2
1611153	Rock		0.098	15	48	2.44	240	0.018	<20	3.05	0.052	0.27	<0.1	0.04	15.8	<0.1	0.09	7	<0.5	<0.2
DUP 1611153	QC		0.097	15	49	2.44	260	0.019	<20	3.07	0.056	0.28	<0.1	0.05	16.0	<0.1	0.09	7	<0.5	<0.2
Reference Materials																				
STD DS10	Standard		0.076	17	55	0.77	397	0.083	<20	1.08	0.071	0.35	3.3	0.31	2.9	5.0	0.27	4	2.2	4.6
STD DS10	Standard		0.070	19	55	0.77	426	0.084	<20	1.07	0.071	0.34	3.5	0.29	2.9	5.3	0.27	4	1.8	5.0
STD DS10	Standard		0.074	18	56	0.79	424	0.085	<20	1.10	0.072	0.34	3.1	0.30	3.0	5.3	0.29	4	2.4	5.2
STD OREAS45EA	Standard		0.029	7	862	0.09	145	0.102	<20	3.39	0.022	0.05	<0.1	0.01	78.1	<0.1	<0.05	12	1.7	<0.2
STD OREAS45EA	Standard		0.026	7	812	0.09	140	0.099	<20	3.38	0.015	0.05	<0.1	0.01	77.4	<0.1	<0.05	12	1.3	<0.2
STD OREAS45EA	Standard		0.028	7	848	0.10	143	0.104	<20	3.52	0.014	0.05	<0.1	0.01	78.1	<0.1	<0.05	12	1.6	<0.2
STD OXC145	Standard																			
STD OXC145	Standard																			



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI17000165.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OXC145	Standard		0.204																		
STD OXH122	Standard		1.207																		
STD OXH122	Standard		1.294																		
STD OXH122	Standard		1.161																		
STD OXN117	Standard		7.523																		
STD OXN117	Standard		7.600																		
STD OXN117	Standard		7.383																		
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXN117 Expected			7.679																		
STD OXC145 Expected			0.212																		
STD OXH122 Expected			1.247																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	1.7	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	0.8	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.6	4.5	1.1	35	<0.1	1.6	4.1	547	1.82	1.0	1.2	2.2	24	<0.1	<0.1	<0.1	23	0.54
ROCK-WHI	Prep Blank		<0.005	0.6	5.4	1.1	35	<0.1	1.7	4.1	538	1.78	0.9	<0.5	2.2	19	<0.1	<0.1	<0.1	23	0.52



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: DIM
Report Date: July 19, 2017

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17000165.1

		AQ200 P % 0.001	AQ200 La ppm 1	AQ200 Cr ppm 1	AQ200 Mg % 0.01	AQ200 Ba ppm 1	AQ200 Ti % 0.001	AQ200 B ppm 20	AQ200 Al % 0.01	AQ200 Na % 0.001	AQ200 K % 0.01	AQ200 W ppm 0.1	AQ200 Hg ppm 0.01	AQ200 Sc ppm 0.1	AQ200 Tl ppm 0.1	AQ200 S % 0.05	AQ200 Ga ppm 1	AQ200 Se ppm 0.5	AQ200 Te ppm 0.2
STD OXC145	Standard																		
STD OXH122	Standard																		
STD OXH122	Standard																		
STD OXH122	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXN117 Expected																			
STD OXC145 Expected																			
STD OXH122 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.038	6	4	0.49	62	0.089	<20	1.01	0.110	0.12	0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.040	5	3	0.46	53	0.084	<20	0.85	0.083	0.09	<0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2