



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada
PHONE (604) 253-3158

Client: **Strike Point Gold**
Suite 507 - 837 W. Hastings St.
Vancouver British Columbia V6C 2X1 Canada

Submitted By: Andy Randell
Receiving Lab: Canada-Whitehorse
Received: July 04, 2017
Report Date: August 05, 2017
Page: 1 of 4

CERTIFICATE OF ANALYSIS

WHI17000227.1

CLIENT JOB INFORMATION

Project: MAHTIN
Shipment ID: SKP RAB 002
P.O. Number: SKPRAB002
Number of Samples: 90

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
STOR-RJT Store After 60 days Invoice for Storage

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Strike Point Gold
Suite 507 - 837 W. Hastings St.
Vancouver British Columbia V6C 2X1
Canada

CC: Scott Dorian
Shawn Khunkhun

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	88	Crush, split and pulverize 250 g rock to 200 mesh			WHI
SLBHP	2	Sort, label and box pulps			WHI
FA430	90	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	90	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	90	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	90	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

2 of 4

Part:

1 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1630300	Rock	1.15	<0.005	0.3	2.8	5.4	29	0.1	3.7	0.5	117	0.16	3.9	2.0	0.2	288	0.2	1.8	<0.1	16	19.90
1630301	Rab Sample	2.54	0.047	1.0	111.8	23.1	54	0.5	15.8	7.5	305	1.58	108.3	11.8	10.7	167	1.7	7.9	2.9	25	2.68
1630302	Rab Sample	2.25	0.005	3.1	867.7	23.4	262	3.5	33.7	23.1	898	3.70	196.3	1.0	8.4	116	46.1	61.0	3.8	28	4.28
1630303	Rab Sample	2.71	0.005	4.0	205.7	20.5	161	2.4	23.4	13.6	1017	3.95	78.8	1.8	7.9	145	18.1	53.2	2.6	22	6.00
1630304	Rab Sample	2.04	<0.005	2.2	95.9	15.8	131	1.1	17.3	12.3	1231	3.44	33.7	1.7	8.8	152	13.0	31.8	1.4	22	6.69
1630305	Rab Sample	2.90	<0.005	3.1	148.3	40.7	84	2.0	14.2	9.0	3058	3.73	44.7	0.5	7.4	122	6.5	70.7	4.3	20	7.46
1630306	Rab Sample	2.49	0.008	2.9	290.0	80.9	85	2.7	20.6	12.4	1824	3.79	718.2	3.1	5.8	90	3.6	80.3	13.6	16	4.41
1630307	Rab Sample	3.36	0.006	3.4	107.4	43.2	119	2.5	24.7	10.4	859	3.22	71.9	2.1	7.2	131	5.6	52.2	3.5	23	6.57
1630308	Rab Sample	3.50	0.005	3.4	88.9	56.2	147	2.3	22.3	7.2	834	2.62	76.3	1.6	8.6	141	7.7	58.8	6.6	22	5.85
1630309	Rab Sample	2.55	0.015	3.3	274.7	160.0	496	2.8	29.0	9.6	928	5.23	517.9	8.8	7.8	71	22.8	122.8	15.9	15	2.80
1630310	Rab Sample	2.11	0.011	2.2	349.7	163.6	256	5.0	35.9	8.7	378	5.90	1055.7	8.6	10.6	28	8.5	170.1	22.6	14	0.37
1630311	Rab Sample	2.97	<0.005	1.8	232.7	33.8	62	1.7	35.8	4.9	241	4.72	209.9	3.4	10.5	20	1.7	55.8	9.6	24	0.45
1630312	Rab Sample	3.29	<0.005	2.6	275.8	41.6	65	3.6	30.9	5.9	189	5.29	722.0	2.8	11.5	26	1.9	59.6	29.4	12	0.25
1630313	Rab Sample	3.33	0.008	2.6	150.7	17.9	40	1.5	24.4	10.6	130	6.39	877.1	12.1	9.6	33	0.3	25.7	23.4	61	0.28
1630314	Rab Sample	3.12	0.009	1.2	77.4	11.7	49	0.4	28.0	11.0	171	3.48	149.8	6.1	9.8	22	0.4	7.2	3.1	66	1.22
1630315	Rab Sample	4.57	0.006	1.6	70.7	37.2	97	0.6	13.3	5.3	219	1.48	155.7	3.0	8.7	282	1.8	17.4	3.1	32	10.05
1630316	Rab Sample	3.89	<0.005	1.0	49.9	24.3	45	0.4	8.2	2.9	208	0.83	83.2	5.7	9.9	309	1.3	14.9	2.0	7	10.74
1630317	Rab Sample	4.42	<0.005	1.0	34.4	16.3	38	0.3	5.7	2.1	180	0.55	44.5	2.3	8.7	300	1.2	9.2	1.3	5	10.70
1630318	Rab Sample	4.33	<0.005	0.9	28.4	12.2	28	0.2	4.9	1.8	151	0.47	34.1	0.8	7.3	355	0.8	6.3	1.0	5	12.49
1630319	Rab Sample	3.85	<0.005	0.8	22.0	8.6	20	0.2	4.0	1.3	133	0.34	25.1	<0.5	6.4	407	0.4	4.7	0.6	4	14.85
1630320	Rock Pulp	0.08	5.165	8.2	196.1	24.3	78	0.8	14.4	11.6	670	4.69	12.6	4894.1	3.4	125	0.1	4.4	0.6	116	1.49
1630321	Rab Sample	4.13	<0.005	1.1	31.7	10.1	19	0.2	4.6	1.8	195	0.41	25.6	1.8	8.5	260	0.7	5.0	0.8	5	12.03
1630322	Rab Sample	3.89	0.010	1.2	35.0	54.6	25	1.9	5.3	2.1	218	0.46	28.1	8.0	8.6	232	0.8	5.5	9.7	5	11.30
1630323	Rab Sample	3.67	<0.005	1.3	21.7	11.8	24	0.2	4.1	1.5	190	0.38	21.8	2.0	8.5	295	0.7	4.6	0.6	5	12.40
1630324	Rab Sample	3.46	<0.005	1.0	24.3	13.4	21	0.2	8.3	3.1	169	0.63	20.6	4.0	9.2	308	0.6	4.1	0.5	10	9.45
1630325	Rab Sample	3.90	<0.005	1.2	30.4	17.5	25	0.2	12.6	4.7	157	0.92	25.4	1.7	10.3	247	0.6	3.3	0.5	19	7.03
1630326	Rab Sample	3.72	<0.005	1.2	24.5	17.6	14	0.2	9.6	3.1	104	0.45	31.7	2.2	9.9	245	0.5	3.5	0.5	7	6.37
1630327	Rab Sample	3.70	0.007	1.4	24.3	14.4	14	0.2	10.5	3.7	136	0.62	27.1	2.0	9.2	270	0.4	3.2	0.7	10	7.60
1630328	Rab Sample	4.06	<0.005	1.2	23.2	19.0	12	0.2	10.4	3.3	117	0.54	22.8	3.6	9.3	280	0.7	3.2	0.3	6	7.24
1630329	Rab Sample	3.73	<0.005	1.3	22.7	18.0	15	0.2	10.8	3.9	160	0.71	21.3	3.9	9.4	294	0.7	3.4	0.4	11	8.77



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

2 of 4

Part:

2 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1630300	Rock	0.016	1	3	12.16	20	0.002	<20	0.08	0.001	0.01	0.2	<0.01	0.4	<0.1	<0.05	<1	<0.5	<0.2			
1630301	Rab Sample	0.127	26	21	0.28	339	0.094	<20	2.40	0.270	0.15	1.5	0.01	2.2	0.1	<0.05	6	<0.5	<0.2			
1630302	Rab Sample	0.149	22	25	0.92	1000	0.003	<20	0.67	0.010	0.29	0.5	0.03	9.7	0.6	0.06	1	0.7	<0.2			
1630303	Rab Sample	0.127	19	22	1.50	592	0.002	<20	0.48	0.003	0.27	0.4	0.03	9.8	0.6	0.09	1	<0.5	<0.2			
1630304	Rab Sample	0.133	20	36	1.41	437	0.001	<20	0.50	0.001	0.31	0.2	0.03	13.3	0.6	0.10	1	<0.5	<0.2			
1630305	Rab Sample	0.130	18	22	1.02	551	0.001	<20	0.30	0.002	0.14	0.3	0.03	6.8	0.3	0.07	<1	<0.5	<0.2			
1630306	Rab Sample	0.081	12	12	0.85	206	<0.001	<20	0.34	0.002	0.15	0.2	0.10	5.2	0.4	0.08	1	2.0	<0.2			
1630307	Rab Sample	0.088	13	12	1.96	529	<0.001	<20	0.42	<0.001	0.24	0.2	0.05	7.3	0.5	0.11	1	<0.5	<0.2			
1630308	Rab Sample	0.137	16	10	1.94	231	0.001	<20	0.38	0.002	0.22	0.4	0.03	5.1	0.4	0.05	1	<0.5	<0.2			
1630309	Rab Sample	0.143	16	8	0.76	47	<0.001	21	0.29	0.002	0.10	0.2	0.10	3.4	0.3	0.08	<1	<0.5	<0.2			
1630310	Rab Sample	0.090	20	9	0.10	74	0.002	44	0.39	0.003	0.13	0.2	0.13	3.1	0.6	0.13	1	0.8	<0.2			
1630311	Rab Sample	0.064	26	17	0.17	74	0.006	24	0.49	0.002	0.18	0.2	0.07	4.8	0.7	0.16	2	<0.5	<0.2			
1630312	Rab Sample	0.053	20	10	0.11	95	0.004	33	0.35	0.004	0.18	0.4	0.04	3.1	0.5	0.21	1	<0.5	<0.2			
1630313	Rab Sample	0.048	24	49	1.14	298	0.102	<20	1.89	0.012	1.03	0.3	0.02	6.8	1.5	0.24	7	<0.5	<0.2			
1630314	Rab Sample	0.051	24	68	2.04	339	0.161	<20	3.10	0.022	1.79	0.2	<0.01	9.5	1.4	0.24	10	<0.5	<0.2			
1630315	Rab Sample	0.086	19	19	0.59	673	0.087	<20	2.81	0.412	0.29	1.0	0.02	2.0	0.2	0.12	7	<0.5	<0.2			
1630316	Rab Sample	0.097	23	12	0.45	316	0.085	<20	2.73	0.497	0.16	1.2	<0.01	0.7	0.1	0.07	7	<0.5	<0.2			
1630317	Rab Sample	0.091	21	8	0.45	724	0.074	<20	2.79	0.532	0.13	1.3	<0.01	0.7	<0.1	<0.05	6	<0.5	<0.2			
1630318	Rab Sample	0.095	19	8	0.09	52	0.072	<20	2.84	0.468	0.11	1.0	<0.01	0.7	<0.1	<0.05	7	<0.5	<0.2			
1630319	Rab Sample	0.102	17	6	0.07	39	0.063	<20	2.70	0.407	0.09	1.0	<0.01	0.6	<0.1	<0.05	7	<0.5	<0.2			
1630320	Rock Pulp	0.054	9	20	0.96	170	0.190	<20	2.69	0.408	0.36	4.0	0.13	5.8	<0.1	<0.05	7	<0.5	<0.2			
1630321	Rab Sample	0.095	20	10	0.09	40	0.073	<20	2.01	0.373	0.11	1.3	<0.01	0.6	<0.1	<0.05	5	<0.5	<0.2			
1630322	Rab Sample	0.107	21	9	0.09	47	0.078	<20	2.32	0.450	0.11	1.7	0.04	0.7	<0.1	<0.05	5	<0.5	<0.2			
1630323	Rab Sample	0.097	22	9	0.08	42	0.077	<20	2.79	0.503	0.13	1.6	<0.01	0.6	<0.1	<0.05	7	<0.5	<0.2			
1630324	Rab Sample	0.092	22	15	0.17	59	0.103	<20	3.11	0.419	0.13	1.6	<0.01	0.9	<0.1	0.09	8	<0.5	<0.2			
1630325	Rab Sample	0.085	24	24	0.37	107	0.132	<20	3.25	0.395	0.29	1.8	<0.01	1.6	0.2	0.11	8	<0.5	<0.2			
1630326	Rab Sample	0.087	24	13	0.11	62	0.104	<20	3.93	0.490	0.11	1.9	<0.01	0.6	<0.1	0.05	10	<0.5	<0.2			
1630327	Rab Sample	0.086	20	16	0.18	85	0.095	<20	3.55	0.481	0.18	5.4	0.01	1.0	0.1	0.08	9	<0.5	<0.2			
1630328	Rab Sample	0.091	19	12	0.08	56	0.089	<20	3.68	0.507	0.10	2.1	<0.01	0.7	<0.1	0.12	9	<0.5	<0.2			
1630329	Rab Sample	0.098	21	18	0.18	76	0.099	<20	3.44	0.471	0.14	2.1	<0.01	1.1	<0.1	0.16	9	<0.5	<0.2			



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

3 of 4

Part:

1 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
1630330	Rab Sample	4.30	<0.005	1.5	26.5	19.3	17	0.3	10.7	4.0	140	0.63	30.7	2.4	9.6	255	0.6	4.0	0.4	10	7.81
1630331	Rab Sample	3.51	<0.005	1.7	19.6	17.3	14	0.2	9.2	3.5	176	0.64	24.2	<0.5	9.8	262	0.4	3.1	0.4	10	9.12
1630332	Rab Sample	3.54	<0.005	1.3	18.1	17.8	11	0.2	8.8	2.9	140	0.49	22.2	1.3	9.4	241	0.5	3.0	0.3	7	8.07
1630333	Rab Sample	3.27	<0.005	1.3	16.0	27.5	12	0.2	6.4	2.0	201	0.47	18.3	1.3	10.1	216	0.6	3.0	0.4	7	10.92
1630334	Rab Sample	3.79	<0.005	1.4	19.6	22.9	13	0.2	7.4	3.0	183	0.52	16.5	1.7	9.7	256	0.7	3.0	0.4	7	10.57
1630335	Rab Sample	3.88	<0.005	1.1	18.8	14.0	8	0.1	6.8	2.7	115	0.34	20.3	0.6	7.0	371	0.5	1.7	0.2	5	14.08
1630336	Rab Sample	3.84	<0.005	0.9	19.0	11.2	13	0.1	7.3	2.7	107	0.43	11.3	1.1	6.6	378	0.3	2.1	0.3	6	13.61
1630337	Rab Sample	3.42	<0.005	1.1	18.2	9.0	16	0.1	4.4	1.7	104	0.39	12.8	1.6	6.9	324	0.5	2.3	0.4	5	11.50
1630338	Rab Sample	3.72	<0.005	1.1	14.7	9.0	13	0.1	4.0	1.1	85	0.31	12.4	1.0	6.5	361	0.4	2.5	0.3	4	12.81
1630339	Rab Sample	3.77	<0.005	1.8	24.5	11.3	21	0.2	4.9	2.0	140	0.50	25.8	0.8	7.2	323	0.5	5.0	0.7	5	12.72
1630340	Rock	1.29	0.012	0.3	1.2	4.5	20	0.1	2.4	0.5	100	0.16	3.1	2.4	0.2	280	0.3	1.5	<0.1	16	20.17
1630341	Rab Sample	3.46	<0.005	1.2	23.6	13.6	18	0.2	4.6	2.0	117	0.36	15.5	0.8	5.3	421	0.5	2.8	0.3	4	15.43
1630342	Rab Sample	3.49	<0.005	0.9	26.9	54.1	46	0.4	4.9	2.0	116	0.40	19.3	3.3	5.1	401	1.0	3.5	1.1	4	16.75
1630343	Rab Sample	4.14	<0.005	1.0	11.2	22.2	12	0.1	5.5	2.1	108	0.35	9.7	1.5	5.7	453	0.3	2.9	0.2	3	17.17
1630344	Rab Sample	3.31	0.006	1.1	9.9	12.7	5	<0.1	5.5	2.3	93	0.30	11.5	<0.5	4.9	489	0.2	2.1	0.2	3	17.55
1630345	Rab Sample	3.42	<0.005	1.1	13.3	13.2	11	0.1	5.7	2.4	127	0.36	9.6	<0.5	6.0	435	0.4	1.9	0.2	6	16.83
1630346	Rab Sample	1.79	<0.005	1.1	15.8	15.1	11	0.2	7.2	3.0	78	0.48	16.9	1.1	7.3	378	0.3	2.9	0.3	6	11.56
1630347	Rab Sample	3.57	<0.005	1.6	17.5	60.4	56	0.7	8.1	3.6	109	0.55	65.4	0.9	9.0	306	1.4	4.4	0.5	6	7.90
1630348	Rab Sample	3.63	0.005	1.4	33.1	59.4	62	0.7	9.7	3.8	143	0.87	182.1	1.6	8.7	241	1.4	4.9	1.1	9	7.58
1630349	Rab Sample	3.46	<0.005	1.5	18.4	50.4	42	0.6	5.9	2.3	98	0.42	13.3	<0.5	7.6	327	1.0	2.8	0.3	5	10.63
1630350	Rab Sample	3.75	<0.005	1.2	18.9	34.2	25	0.3	7.3	2.6	99	0.42	10.2	0.9	5.7	384	0.6	2.1	0.4	5	14.47
1630351	Rab Sample	3.53	<0.005	1.1	10.6	10.0	4	<0.1	7.7	2.4	77	0.33	7.0	0.6	5.2	461	<0.1	1.1	0.2	4	15.50
1630352	Rab Sample	3.49	<0.005	1.3	12.2	14.9	12	0.1	5.5	1.7	87	0.32	9.9	<0.5	6.5	394	0.3	1.4	0.2	4	12.80
1630353	Rab Sample	3.90	<0.005	1.4	11.4	15.3	12	0.1	5.9	1.9	85	0.32	7.7	1.2	7.0	346	0.3	1.1	0.5	4	11.92
1630354	Rab Sample	3.47	<0.005	1.3	12.1	22.9	9	<0.1	6.5	2.5	100	0.41	6.6	1.0	7.0	332	0.2	1.0	0.2	5	12.40
1630355	Rab Sample	2.93	<0.005	1.2	11.5	12.7	4	<0.1	7.3	2.3	64	0.32	5.2	0.9	5.9	397	0.1	0.8	<0.1	3	13.26
1630356	Rab Sample	3.74	<0.005	1.2	12.1	10.0	4	<0.1	6.8	2.0	65	0.31	6.8	1.3	6.4	403	0.1	0.7	0.1	4	12.32
1630357	Rab Sample	3.53	<0.005	1.5	12.0	11.7	6	<0.1	7.5	2.6	100	0.45	8.8	<0.5	7.4	337	0.1	0.9	<0.1	5	11.31
1630358	Rab Sample	3.94	0.005	1.3	16.2	11.6	31	0.1	15.9	7.1	178	1.53	13.0	1.8	8.4	458	0.2	0.7	0.1	31	12.11
1630359	Rab Sample	4.39	<0.005	1.1	10.3	8.1	4	<0.1	5.4	1.7	85	0.28	8.3	<0.5	6.0	368	<0.1	1.0	<0.1	3	13.29



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

3 of 4

Part:

2 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1630330	Rab Sample	0.100	21	17	0.15	69	0.096	<20	3.13	0.440	0.13	2.1	<0.01	0.9	<0.1	0.13	8	<0.5	<0.2			
1630331	Rab Sample	0.103	21	16	0.18	80	0.092	<20	2.98	0.449	0.18	2.2	<0.01	1.0	0.1	0.10	8	<0.5	<0.2			
1630332	Rab Sample	0.096	20	12	0.10	51	0.087	<20	2.81	0.456	0.10	1.9	<0.01	0.7	<0.1	0.08	7	<0.5	<0.2			
1630333	Rab Sample	0.111	23	11	0.10	64	0.093	<20	2.18	0.428	0.12	1.7	<0.01	0.6	<0.1	0.06	6	<0.5	<0.2			
1630334	Rab Sample	0.101	22	13	0.12	55	0.087	<20	2.50	0.419	0.11	2.0	<0.01	0.6	<0.1	0.08	6	<0.5	<0.2			
1630335	Rab Sample	0.075	16	10	0.07	42	0.077	<20	2.85	0.370	0.08	1.2	<0.01	0.4	<0.1	0.07	7	<0.5	<0.2			
1630336	Rab Sample	0.073	16	11	0.12	46	0.080	21	3.49	0.437	0.12	0.6	<0.01	0.6	<0.1	0.08	8	<0.5	<0.2			
1630337	Rab Sample	0.073	17	10	0.11	48	0.077	<20	3.53	0.459	0.12	1.0	<0.01	0.5	<0.1	<0.05	9	<0.5	<0.2			
1630338	Rab Sample	0.088	15	8	0.07	45	0.075	<20	3.43	0.451	0.11	0.7	<0.01	0.4	<0.1	<0.05	8	<0.5	<0.2			
1630339	Rab Sample	0.087	16	12	0.08	56	0.069	27	3.01	0.381	0.10	1.3	0.01	0.6	<0.1	<0.05	8	<0.5	<0.2			
1630340	Rock	0.013	1	3	11.50	15	0.002	<20	0.10	0.002	0.04	0.2	<0.01	0.3	<0.1	<0.05	<1	<0.5	<0.2			
1630341	Rab Sample	0.074	13	8	0.08	41	0.062	<20	2.63	0.324	0.11	0.6	0.02	0.4	<0.1	0.07	6	<0.5	<0.2			
1630342	Rab Sample	0.078	13	8	0.07	38	0.063	<20	2.41	0.287	0.10	0.6	0.02	0.4	<0.1	0.11	6	<0.5	<0.2			
1630343	Rab Sample	0.077	13	7	0.08	36	0.060	<20	2.29	0.245	0.08	0.6	<0.01	0.5	<0.1	0.08	6	<0.5	<0.2			
1630344	Rab Sample	0.081	11	6	0.07	35	0.057	<20	2.07	0.231	0.08	0.6	<0.01	0.4	<0.1	0.08	5	<0.5	<0.2			
1630345	Rab Sample	0.089	14	10	0.12	50	0.059	<20	2.72	0.331	0.13	0.7	<0.01	0.5	<0.1	0.07	6	<0.5	<0.2			
1630346	Rab Sample	0.096	17	10	0.13	46	0.072	<20	3.83	0.399	0.12	0.8	<0.01	0.7	<0.1	0.09	8	<0.5	<0.2			
1630347	Rab Sample	0.103	21	13	0.15	59	0.089	46	3.60	0.445	0.11	1.4	<0.01	0.6	<0.1	0.12	9	<0.5	<0.2			
1630348	Rab Sample	0.105	20	16	0.24	39	0.081	28	2.90	0.372	0.11	1.9	<0.01	1.0	0.2	0.29	8	<0.5	<0.2			
1630349	Rab Sample	0.102	19	11	0.08	56	0.093	29	3.58	0.483	0.13	1.3	<0.01	0.5	<0.1	0.09	9	<0.5	<0.2			
1630350	Rab Sample	0.090	15	10	0.09	42	0.079	<20	3.03	0.332	0.10	0.8	<0.01	0.4	<0.1	0.11	8	<0.5	<0.2			
1630351	Rab Sample	0.094	13	7	0.07	35	0.066	<20	2.91	0.342	0.08	0.6	0.01	0.4	<0.1	0.10	6	<0.5	<0.2			
1630352	Rab Sample	0.092	16	9	0.07	37	0.073	<20	3.54	0.471	0.10	1.0	<0.01	0.5	<0.1	<0.05	8	<0.5	<0.2			
1630353	Rab Sample	0.090	17	10	0.05	34	0.069	<20	3.47	0.485	0.11	1.3	<0.01	0.3	<0.1	0.06	8	<0.5	<0.2			
1630354	Rab Sample	0.092	17	11	0.09	44	0.070	<20	3.12	0.443	0.11	1.1	<0.01	0.4	<0.1	0.10	7	<0.5	<0.2			
1630355	Rab Sample	0.085	15	8	0.07	38	0.068	<20	3.34	0.386	0.08	0.7	<0.01	0.4	<0.1	0.09	8	<0.5	<0.2			
1630356	Rab Sample	0.084	16	9	0.07	37	0.074	<20	3.77	0.384	0.07	0.8	<0.01	0.4	<0.1	0.06	8	<0.5	<0.2			
1630357	Rab Sample	0.091	17	12	0.10	45	0.076	<20	3.51	0.462	0.10	1.0	<0.01	0.5	<0.1	0.11	8	<0.5	<0.2			
1630358	Rab Sample	0.101	21	37	0.82	280	0.123	<20	4.74	0.376	0.69	1.1	<0.01	3.7	0.3	0.27	12	<0.5	<0.2			
1630359	Rab Sample	0.095	15	9	0.05	37	0.065	<20	3.31	0.383	0.07	0.8	<0.01	0.5	<0.1	0.05	8	<0.5	<0.2			



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

4 of 4

Part:

1 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1630360	Rock Pulp	0.10	4.807	8.1	196.2	23.1	77	0.9	15.2	11.2	593	4.34	12.4	5444.4	2.9	73	0.2	4.0	0.5	106	0.93
1630361	Rab Sample	3.65	0.006	1.3	17.3	10.1	27	<0.1	15.5	6.8	164	1.60	11.0	2.4	8.4	425	0.1	0.9	0.2	27	12.99
1630362	Rab Sample	3.52	0.005	1.8	17.2	14.5	23	<0.1	13.9	5.6	138	1.11	10.9	5.7	9.0	290	0.2	1.1	0.2	18	8.63
1630363	Rab Sample	3.36	<0.005	1.6	14.2	11.0	21	<0.1	13.2	5.3	132	1.06	12.6	5.0	8.4	332	0.2	1.3	0.2	21	10.53
1630364	Rab Sample	3.57	<0.005	1.5	13.2	8.9	22	<0.1	13.0	5.2	207	1.19	6.8	2.4	7.4	439	0.2	1.1	0.2	22	13.78
1630365	Rab Sample	3.60	<0.005	1.6	12.0	10.3	6	<0.1	9.1	3.1	127	0.54	6.1	2.6	7.0	291	0.1	1.3	0.1	5	12.21
1630366	Rab Sample	3.53	<0.005	1.6	13.4	13.1	8	<0.1	10.1	3.3	140	0.56	7.5	3.1	7.0	325	0.1	1.2	0.1	6	13.09
1630367	Rab Sample	3.62	<0.005	1.5	12.8	16.1	9	<0.1	9.3	3.2	143	0.55	6.7	2.4	7.3	327	0.2	0.9	0.1	6	13.06
1630368	Rab Sample	3.32	<0.005	1.5	13.5	10.4	6	<0.1	8.1	2.7	114	0.44	7.4	1.5	6.7	326	0.2	1.2	0.1	4	12.56
1630369	Rab Sample	3.55	<0.005	1.1	12.5	9.9	4	<0.1	6.7	2.4	103	0.38	4.8	1.2	6.2	359	<0.1	1.3	0.1	4	13.21
1630370	Rab Sample	2.94	<0.005	1.4	12.6	9.5	5	<0.1	6.3	2.4	88	0.44	5.7	0.8	6.1	328	<0.1	0.9	0.1	4	11.62
1630371	Rab Sample	3.72	<0.005	1.1	11.4	11.0	6	<0.1	6.1	2.5	104	0.49	5.7	2.2	6.2	352	<0.1	1.3	0.2	5	13.65
1630372	Rab Sample	2.56	<0.005	1.0	29.2	17.6	20	0.2	8.6	3.2	151	0.77	47.0	1.1	6.8	355	0.6	10.0	1.3	6	11.74
1630373	Rab Sample	2.94	<0.005	1.7	11.9	12.2	6	<0.1	6.3	2.5	96	0.46	5.3	0.7	6.1	388	0.1	1.1	0.1	4	14.04
1630374	Rab Sample	2.82	<0.005	1.8	11.1	11.9	5	<0.1	6.4	2.2	99	0.44	4.8	1.5	6.0	387	<0.1	0.7	<0.1	4	13.99
1630375	Rab Sample	4.28	<0.005	1.7	12.8	13.8	10	<0.1	7.4	2.7	112	0.56	4.6	1.1	6.3	378	<0.1	0.6	<0.1	6	14.08
1630376	Rab Sample	4.32	<0.005	1.7	10.9	13.1	7	<0.1	6.2	2.3	105	0.50	4.5	1.5	5.9	391	0.1	0.6	<0.1	5	14.30
1630377	Rab Sample	3.96	0.005	1.9	12.7	12.5	8	<0.1	5.8	2.1	84	0.48	5.5	2.9	6.3	292	0.2	0.7	<0.1	5	11.85
1630378	Rab Sample	4.18	<0.005	1.9	13.0	14.6	7	<0.1	5.8	2.1	83	0.46	4.6	1.3	7.0	266	0.2	0.5	<0.1	5	10.24
1630379	Rab Sample	3.23	<0.005	1.6	10.7	13.4	8	<0.1	5.9	2.0	110	0.42	4.2	3.6	6.1	358	0.2	0.6	<0.1	4	14.65
1630380	Rock	1.05	<0.005	0.3	1.1	4.2	20	0.1	2.2	0.4	98	0.16	3.1	2.1	0.2	270	0.2	1.3	<0.1	16	19.26
1630381	Rab Sample	3.87	<0.005	1.8	9.4	17.9	7	<0.1	6.6	2.0	115	0.38	6.4	1.9	5.7	401	0.2	0.7	<0.1	4	15.51
1630382	Rab Sample	4.18	<0.005	1.8	10.4	18.4	6	<0.1	5.1	1.7	113	0.38	4.8	<0.5	6.9	398	0.3	0.5	<0.1	4	13.84
1630383	Rab Sample	3.51	<0.005	1.6	9.2	21.2	6	<0.1	4.6	1.7	116	0.37	4.5	0.9	6.9	375	0.2	0.6	<0.1	3	14.59
1630384	Rab Sample	3.91	<0.005	1.8	14.4	20.8	6	<0.1	5.9	2.1	101	0.42	5.8	8.4	6.4	394	0.1	0.6	<0.1	4	14.45
1630385	Rab Sample	4.20	<0.005	1.7	20.0	14.3	7	<0.1	6.9	2.3	96	0.41	4.7	6.2	6.0	404	<0.1	0.6	<0.1	5	13.75
1630386	Rab Sample	3.37	<0.005	1.8	13.9	15.0	9	<0.1	5.8	2.1	99	0.48	6.1	<0.5	6.5	361	0.2	0.9	<0.1	5	13.06
1630387	Rab Sample	3.96	<0.005	1.5	11.3	14.0	9	<0.1	5.5	1.8	90	0.37	5.7	2.0	6.1	357	0.1	0.7	<0.1	4	13.43
1630388	Rab Sample	3.88	<0.005	1.6	11.7	12.4	14	<0.1	7.3	2.8	139	0.57	7.5	2.1	6.2	401	0.2	0.8	<0.1	7	13.97
1630389	Rab Sample	2.84	<0.005	2.5	14.4	10.3	13	<0.1	10.2	2.9	118	0.58	7.6	2.3	6.2	357	<0.1	1.1	<0.1	6	12.36



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

4 of 4

Part:

2 of 2

CERTIFICATE OF ANALYSIS

WHI17000227.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1630360	Rock Pulp	0.062	7	19	0.89	133	0.148	<20	1.78	0.193	0.24	5.1	0.16	3.1	<0.1	<0.05	5	<0.5	<0.2
1630361	Rab Sample	0.110	21	33	0.83	264	0.125	<20	4.68	0.296	0.61	0.9	<0.01	3.4	0.2	0.28	12	<0.5	<0.2
1630362	Rab Sample	0.085	21	28	0.47	164	0.109	<20	3.83	0.389	0.35	2.1	<0.01	2.2	0.1	0.20	10	<0.5	<0.2
1630363	Rab Sample	0.087	19	27	0.51	197	0.124	<20	4.28	0.444	0.50	1.2	<0.01	2.5	0.1	0.15	11	<0.5	<0.2
1630364	Rab Sample	0.092	18	31	0.58	225	0.115	<20	3.35	0.273	0.51	1.0	<0.01	3.3	0.2	0.18	9	<0.5	<0.2
1630365	Rab Sample	0.093	18	14	0.13	62	0.077	<20	2.99	0.377	0.09	1.2	<0.01	0.6	<0.1	0.15	8	<0.5	<0.2
1630366	Rab Sample	0.095	18	15	0.14	67	0.078	<20	3.15	0.390	0.11	1.3	<0.01	0.6	<0.1	0.16	8	<0.5	<0.2
1630367	Rab Sample	0.106	20	14	0.14	68	0.081	<20	2.96	0.374	0.10	1.3	<0.01	0.7	<0.1	0.16	8	<0.5	<0.2
1630368	Rab Sample	0.097	17	11	0.09	52	0.069	<20	3.04	0.391	0.08	0.9	<0.01	0.5	<0.1	0.11	8	<0.5	<0.2
1630369	Rab Sample	0.103	15	10	0.07	41	0.070	<20	3.00	0.350	0.07	1.0	<0.01	0.5	<0.1	0.09	7	<0.5	<0.2
1630370	Rab Sample	0.094	14	11	0.09	44	0.064	<20	3.46	0.411	0.08	0.9	<0.01	0.5	<0.1	0.11	8	<0.5	<0.2
1630371	Rab Sample	0.108	15	11	0.15	79	0.065	<20	3.17	0.299	0.12	0.9	<0.01	0.3	<0.1	0.13	8	<0.5	<0.2
1630372	Rab Sample	0.114	16	10	0.18	201	0.053	<20	3.18	0.329	0.11	0.7	<0.01	1.0	<0.1	0.12	9	<0.5	<0.2
1630373	Rab Sample	0.109	15	12	0.13	62	0.066	<20	3.08	0.335	0.10	1.0	<0.01	0.5	<0.1	0.11	7	<0.5	<0.2
1630374	Rab Sample	0.111	16	13	0.14	67	0.065	<20	3.11	0.347	0.10	0.9	<0.01	0.5	<0.1	0.10	8	<0.5	<0.2
1630375	Rab Sample	0.115	16	15	0.18	78	0.077	<20	3.27	0.383	0.13	1.1	<0.01	0.6	<0.1	0.14	8	<0.5	<0.2
1630376	Rab Sample	0.107	14	15	0.16	68	0.070	<20	3.19	0.369	0.13	1.1	<0.01	0.7	<0.1	0.12	8	<0.5	<0.2
1630377	Rab Sample	0.106	15	14	0.12	61	0.072	<20	3.30	0.323	0.12	1.3	<0.01	0.7	<0.1	0.10	8	<0.5	<0.2
1630378	Rab Sample	0.100	16	15	0.11	49	0.071	<20	3.54	0.386	0.10	1.4	<0.01	0.6	<0.1	0.08	9	<0.5	<0.2
1630379	Rab Sample	0.117	15	12	0.11	54	0.063	<20	2.86	0.324	0.11	1.0	<0.01	0.7	<0.1	0.10	7	<0.5	<0.2
1630380	Rock	0.015	1	3	10.98	15	0.002	<20	0.08	0.002	0.08	0.2	<0.01	0.4	<0.1	<0.05	<1	<0.5	<0.2
1630381	Rab Sample	0.107	14	12	0.07	42	0.064	<20	2.91	0.350	0.12	1.0	<0.01	0.5	<0.1	0.09	7	<0.5	<0.2
1630382	Rab Sample	0.104	16	12	0.08	42	0.063	<20	3.16	0.350	0.11	1.2	<0.01	0.5	<0.1	0.08	8	<0.5	<0.2
1630383	Rab Sample	0.106	15	12	0.08	42	0.062	<20	2.91	0.396	0.11	1.0	<0.01	0.5	<0.1	0.07	7	<0.5	<0.2
1630384	Rab Sample	0.112	15	12	0.10	53	0.064	<20	3.11	0.357	0.08	0.9	<0.01	0.4	<0.1	0.10	8	<0.5	<0.2
1630385	Rab Sample	0.108	14	12	0.11	43	0.062	<20	3.26	0.320	0.08	1.1	<0.01	0.7	<0.1	0.09	8	<0.5	<0.2
1630386	Rab Sample	0.108	15	15	0.14	55	0.071	<20	3.42	0.409	0.11	1.4	<0.01	0.7	<0.1	0.08	8	<0.5	<0.2
1630387	Rab Sample	0.103	14	12	0.08	47	0.063	<20	3.24	0.387	0.08	1.1	<0.01	0.5	<0.1	0.07	8	<0.5	<0.2
1630388	Rab Sample	0.108	15	16	0.20	85	0.067	<20	3.03	0.382	0.19	1.0	<0.01	0.9	<0.1	0.11	8	<0.5	<0.2
1630389	Rab Sample	0.112	17	17	0.16	66	0.070	<20	3.15	0.355	0.12	1.4	<0.01	0.8	<0.1	0.14	8	<0.5	<0.2



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

1 of 2

Part:

1 of 2

QUALITY CONTROL REPORT

WHI17000227.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
Pulp Duplicates																					
1630301	Rab Sample	2.54	0.047	1.0	111.8	23.1	54	0.5	15.8	7.5	305	1.58	108.3	11.8	10.7	167	1.7	7.9	2.9	25	2.68
REP 1630301	QC			1.0	111.8	23.0	52	0.5	16.2	7.8	299	1.57	109.2	36.1	10.7	168	1.9	7.8	3.0	25	2.66
REP 1630324	QC	0.005																			
1630332	Rab Sample	3.54	<0.005	1.3	18.1	17.8	11	0.2	8.8	2.9	140	0.49	22.2	1.3	9.4	241	0.5	3.0	0.3	7	8.07
REP 1630332	QC			1.4	18.6	18.2	11	0.2	8.5	3.0	139	0.49	21.6	2.3	9.8	240	0.4	3.1	0.3	7	8.23
1630364	Rab Sample	3.57	<0.005	1.5	13.2	8.9	22	<0.1	13.0	5.2	207	1.19	6.8	2.4	7.4	439	0.2	1.1	0.2	22	13.78
REP 1630364	QC	<0.005																			
1630366	Rab Sample	3.53	<0.005	1.6	13.4	13.1	8	<0.1	10.1	3.3	140	0.56	7.5	3.1	7.0	325	0.1	1.2	0.1	6	13.09
REP 1630366	QC		<0.005	1.8	12.9	12.7	8	<0.1	8.8	3.4	136	0.56	7.2	1.8	7.0	320	0.1	1.3	0.1	6	12.89
Core Reject Duplicates																					
1630324	Rab Sample	3.46	<0.005	1.0	24.3	13.4	21	0.2	8.3	3.1	169	0.63	20.6	4.0	9.2	308	0.6	4.1	0.5	10	9.45
DUP 1630324	QC		<0.005	1.1	23.7	13.2	18	0.2	8.6	3.3	171	0.64	22.7	4.3	9.4	318	0.7	4.2	0.5	10	9.71
1630358	Rab Sample	3.94	0.005	1.3	16.2	11.6	31	0.1	15.9	7.1	178	1.53	13.0	1.8	8.4	458	0.2	0.7	0.1	31	12.11
DUP 1630358	QC		<0.005	1.2	15.6	11.8	30	0.1	14.7	6.8	183	1.55	12.8	1.7	8.2	453	0.2	0.5	0.1	32	12.38
Reference Materials																					
STD DS10	Standard			12.4	155.8	132.7	344	1.8	66.5	11.9	875	2.76	41.6	52.7	7.0	69	2.3	7.5	12.5	44	1.02
STD DS10	Standard			12.5	154.0	142.4	361	1.7	74.3	12.5	853	2.71	46.1	50.0	6.6	65	2.5	7.7	11.2	42	1.05
STD DS10	Standard			13.3	154.7	161.1	367	1.8	74.0	13.2	895	2.81	46.3	57.4	7.6	67	2.4	7.8	12.7	43	1.07
STD OREAS45EA	Standard			1.6	726.6	15.5	33	0.3	384.4	53.5	420	23.48	12.8	53.8	12.2	4	<0.1	0.3	0.4	312	0.03
STD OREAS45EA	Standard			1.6	694.2	13.4	30	0.2	382.7	51.3	406	21.31	10.2	52.9	9.7	4	<0.1	0.3	0.2	309	0.04
STD OREAS45EA	Standard			1.5	690.4	14.1	30	0.2	378.3	51.7	391	21.64	10.1	53.3	9.9	4	<0.1	0.3	0.4	306	0.04
STD OXC145	Standard	0.198																			
STD OXC145	Standard	0.207																			
STD OXH122	Standard	1.218																			
STD OXH122	Standard	1.218																			
STD OXN117	Standard	7.425																			
STD OXN117	Standard	7.743																			
STD DS10 Expected				13.6	154.61	150.55	370	2.02	74.6	12.9	875	2.7188	46.2	91.9	7.5	67.1	2.62	9	11.65	43	1.0625



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

1 of 2

Part:

2 of 2

QUALITY CONTROL REPORT

WHI17000227.1

	Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
	Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
	MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1630301	Rab Sample	0.127	26	21	0.28	339	0.094	<20	2.40	0.270	0.15	1.5	0.01	2.2	0.1	<0.05	6	<0.5	<0.2
REP 1630301	QC	0.119	26	20	0.29	347	0.094	<20	2.40	0.271	0.16	1.3	0.02	2.2	0.2	<0.05	6	<0.5	<0.2
REP 1630324	QC																		
1630332	Rab Sample	0.096	20	12	0.10	51	0.087	<20	2.81	0.456	0.10	1.9	<0.01	0.7	<0.1	0.08	7	<0.5	<0.2
REP 1630332	QC	0.098	20	13	0.11	51	0.089	<20	2.83	0.457	0.10	1.7	<0.01	0.7	<0.1	0.08	7	<0.5	<0.2
1630364	Rab Sample	0.092	18	31	0.58	225	0.115	<20	3.35	0.273	0.51	1.0	<0.01	3.3	0.2	0.18	9	<0.5	<0.2
REP 1630364	QC																		
1630366	Rab Sample	0.095	18	15	0.14	67	0.078	<20	3.15	0.390	0.11	1.3	<0.01	0.6	<0.1	0.16	8	<0.5	<0.2
REP 1630366	QC	0.096	18	14	0.14	69	0.079	<20	3.14	0.390	0.11	1.4	<0.01	0.5	<0.1	0.16	8	<0.5	<0.2
Core Reject Duplicates																			
1630324	Rab Sample	0.092	22	15	0.17	59	0.103	<20	3.11	0.419	0.13	1.6	<0.01	0.9	<0.1	0.09	8	<0.5	<0.2
DUP 1630324	QC	0.088	21	16	0.17	60	0.102	<20	3.12	0.422	0.13	1.7	<0.01	0.8	<0.1	0.10	8	<0.5	<0.2
1630358	Rab Sample	0.101	21	37	0.82	280	0.123	<20	4.74	0.376	0.69	1.1	<0.01	3.7	0.3	0.27	12	<0.5	<0.2
DUP 1630358	QC	0.101	20	37	0.83	281	0.126	<20	4.67	0.383	0.70	1.1	<0.01	3.7	0.3	0.27	11	<0.5	<0.2
Reference Materials																			
STD DS10	Standard	0.082	18	52	0.80	372	0.087	<20	1.06	0.070	0.33	2.7	0.25	2.7	4.6	0.28	4	1.3	4.4
STD DS10	Standard	0.072	16	53	0.76	400	0.078	<20	1.01	0.069	0.34	3.4	0.25	2.9	5.1	0.28	4	2.2	4.7
STD DS10	Standard	0.076	17	55	0.78	431	0.081	<20	1.05	0.072	0.35	3.7	0.31	2.8	5.3	0.29	4	1.9	4.9
STD OREAS45EA	Standard	0.029	8	847	0.10	150	0.110	<20	3.52	0.020	0.06	<0.1	0.01	82.6	<0.1	<0.05	13	0.9	<0.2
STD OREAS45EA	Standard	0.030	7	856	0.10	142	0.100	<20	3.16	0.016	0.06	<0.1	<0.01	81.8	<0.1	<0.05	12	0.6	<0.2
STD OREAS45EA	Standard	0.029	7	822	0.09	140	0.101	<20	3.20	0.017	0.06	<0.1	0.01	79.8	<0.1	<0.05	12	<0.5	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH122	Standard																		
STD OXH122	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD DS10 Expected		0.0765	17.5	54.6	0.775	412	0.0817		1.0259	0.067	0.338	3.32	0.3	2.8	5.1	0.29	4.3	2.3	5.01



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

2 of 2

Part:

1 of 2

QUALITY CONTROL REPORT

WHI17000227.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD OXN117 Expected			7.679																		
STD OXC145 Expected			0.212																		
STD OXH122 Expected			1.247																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.5	10.8	1.2	35	<0.1	0.9	3.4	515	1.63	0.9	0.7	2.1	21	<0.1	<0.1	<0.1	20	0.51
ROCK-WHI	Prep Blank		<0.005	0.6	5.5	1.2	34	<0.1	0.8	3.6	548	1.70	1.8	<0.5	2.3	22	<0.1	<0.1	<0.1	21	0.53



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

Strike Point Gold

Suite 507 - 837 W. Hastings St.

Vancouver British Columbia V6C 2X1 Canada

Project:

MAHTIN

Report Date:

August 05, 2017

Page:

2 of 2

Part:

2 of 2

QUALITY CONTROL REPORT

WHI17000227.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD OXN117 Expected																			
STD OXC145 Expected																			
STD OXH122 Expected																			
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.042	5	5	0.47	48	0.089	<20	0.83	0.071	0.09	0.1	<0.01	2.5	<0.1	<0.05	3	<0.5	<0.2
ROCK-WHI	Prep Blank	0.042	6	6	0.50	47	0.088	<20	0.85	0.072	0.09	0.1	<0.01	2.6	<0.1	<0.05	3	<0.5	<0.2