



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Submitted By: Jodie Gibson

Receiving Lab: Canada-Whitehorse

Received: October 23, 2017

Report Date: November 17, 2017

Page: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17001090.1

CLIENT JOB INFORMATION

Project: WHT
Shipment ID: WHT20171020-004-ROCK
P.O. Number
Number of Samples: 16

SAMPLE DISPOSAL

RTRN-PLP Return After 90 days
PICKUP-RJT Client to Pickup Rejects

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	16	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	16	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	16	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	16	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	16	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.
Box 70
Dawson Yukon Y0B 1G0
Canada

CC: Isaac Fage
Shawn Ryan
Greg Dawson



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 2 of 2

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI17001090.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1602622	Rock	1.43	<0.005	0.3	66.6	1.0	12	<0.1	19.6	8.6	117	0.77	2.7	1.6	0.3	14	<0.1	<0.1	<0.1	21	0.66
1602623	Rock	0.77	<0.005	0.3	59.2	0.8	9	<0.1	21.0	5.6	91	0.56	7.2	2.9	0.2	27	<0.1	0.1	<0.1	15	0.63
1602624	Rock	0.67	<0.005	0.3	55.2	0.8	9	<0.1	22.8	6.4	97	0.62	3.0	<0.5	0.1	11	<0.1	<0.1	<0.1	16	0.67
1602625	Rock	0.65	<0.005	0.2	72.1	2.5	19	<0.1	34.5	14.5	167	1.38	6.1	1.2	0.9	19	<0.1	0.2	<0.1	31	0.62
1602627	Rock	0.98	<0.005	0.2	56.4	5.3	10	<0.1	22.2	7.6	115	0.73	3.6	<0.5	0.4	13	<0.1	<0.1	<0.1	18	0.64
1602628	Rock	0.73	<0.005	0.3	86.1	2.4	14	<0.1	43.4	18.6	206	1.12	1.5	<0.5	1.1	34	<0.1	0.1	<0.1	34	0.93
1602629	Rock	1.01	0.012	<0.1	120.2	0.8	14	<0.1	43.8	13.4	273	1.23	1.2	10.2	<0.1	36	<0.1	<0.1	<0.1	39	0.83
1602630	Rock	0.43	0.031	0.1	62.0	1.2	13	<0.1	32.1	12.2	190	1.03	2.8	24.8	0.3	23	<0.1	0.1	<0.1	27	0.76
1602631	Rock	0.91	0.011	0.2	63.6	1.5	12	<0.1	27.2	9.8	150	0.88	3.1	11.6	0.3	29	<0.1	0.2	<0.1	25	0.71
1602632	Rock	0.61	0.012	0.2	79.3	1.2	16	<0.1	23.6	9.9	214	1.21	2.0	9.4	0.4	21	<0.1	0.1	<0.1	38	0.87
1602633	Rock	0.94	0.012	0.2	80.9	1.1	11	<0.1	17.5	7.9	140	0.87	2.0	10.1	0.4	18	<0.1	<0.1	<0.1	26	0.70
1602634	Rock	0.64	0.010	0.2	77.6	1.9	17	<0.1	30.7	13.6	175	1.09	4.3	11.0	0.8	23	<0.1	0.2	<0.1	28	0.60
1602635	Rock	1.15	<0.005	0.3	65.8	0.7	8	<0.1	26.1	9.7	111	0.64	3.4	4.0	0.2	12	<0.1	<0.1	<0.1	14	0.52
1602636	Rock	0.86	<0.005	0.2	39.6	0.9	9	<0.1	13.9	5.9	102	0.77	3.2	3.6	0.4	12	<0.1	<0.1	<0.1	19	0.55
1602637	Rock	0.96	<0.005	0.3	44.3	1.1	11	<0.1	15.2	7.1	152	0.81	3.2	4.4	0.3	11	<0.1	<0.1	<0.1	17	0.49
1602638	Rock	1.00	<0.005	0.2	57.3	1.1	10	<0.1	18.7	8.1	115	0.71	1.6	4.2	0.5	14	<0.1	<0.1	<0.1	19	0.58



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 2 of 2

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI17001090.1

		Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
			%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
			0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1602622	Rock		0.002	1	26	0.43	26	0.094	<20	0.72	0.042	0.01	0.1	<0.01	3.7	<0.1	<0.05	1	<0.5	<0.2
1602623	Rock		0.005	<1	20	0.25	29	0.094	<20	0.65	0.031	0.01	<0.1	<0.01	3.3	<0.1	<0.05	1	<0.5	<0.2
1602624	Rock		0.003	<1	24	0.39	16	0.096	<20	0.68	0.048	0.01	<0.1	<0.01	3.0	<0.1	<0.05	1	<0.5	<0.2
1602625	Rock		0.014	4	28	0.58	58	0.077	<20	1.20	0.041	0.03	<0.1	<0.01	3.8	<0.1	<0.05	2	<0.5	<0.2
1602627	Rock		0.005	2	18	0.39	27	0.076	<20	0.72	0.050	0.01	0.1	<0.01	3.0	<0.1	<0.05	1	<0.5	<0.2
1602628	Rock		0.004	1	62	0.83	20	0.097	<20	1.40	0.030	0.02	<0.1	<0.01	6.0	<0.1	<0.05	3	<0.5	<0.2
1602629	Rock		0.001	<1	82	1.30	24	0.099	<20	1.40	0.026	0.03	<0.1	0.01	7.1	<0.1	<0.05	3	<0.5	<0.2
1602630	Rock		0.004	2	40	0.82	48	0.076	<20	1.19	0.047	0.03	<0.1	0.01	4.7	<0.1	<0.05	2	<0.5	<0.2
1602631	Rock		0.005	2	53	0.58	44	0.095	<20	0.92	0.035	0.02	<0.1	<0.01	4.2	<0.1	<0.05	2	<0.5	<0.2
1602632	Rock		0.019	2	38	0.63	48	0.109	<20	1.09	0.071	0.03	0.1	<0.01	4.5	<0.1	<0.05	2	<0.5	<0.2
1602633	Rock		0.006	2	42	0.48	37	0.109	<20	0.88	0.039	0.02	<0.1	<0.01	4.3	<0.1	<0.05	2	<0.5	<0.2
1602634	Rock		0.010	3	45	0.47	63	0.076	<20	0.92	0.035	0.03	<0.1	<0.01	4.2	<0.1	<0.05	2	<0.5	<0.2
1602635	Rock		0.003	<1	39	0.31	16	0.077	<20	0.59	0.031	0.01	<0.1	<0.01	2.8	<0.1	<0.05	1	<0.5	<0.2
1602636	Rock		0.007	2	31	0.32	34	0.077	<20	0.72	0.039	0.02	<0.1	<0.01	2.6	<0.1	<0.05	1	<0.5	<0.2
1602637	Rock		0.008	1	31	0.27	20	0.091	<20	0.65	0.029	0.01	<0.1	<0.01	2.7	<0.1	<0.05	1	<0.5	<0.2
1602638	Rock		0.003	3	28	0.36	34	0.087	<20	0.77	0.039	0.02	<0.1	<0.01	3.1	<0.1	<0.05	1	<0.5	<0.2



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 1 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI17001090.1

Method Analyte Unit MDL		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
Pulp Duplicates																					
1602637	Rock	0.96	<0.005	0.3	44.3	1.1	11	<0.1	15.2	7.1	152	0.81	3.2	4.4	0.3	11	<0.1	<0.1	<0.1	17	0.49
REP 1602637	QC		<0.005																		
Core Reject Duplicates																					
1602624	Rock	0.67	<0.005	0.3	55.2	0.8	9	<0.1	22.8	6.4	97	0.62	3.0	<0.5	0.1	11	<0.1	<0.1	<0.1	16	0.67
DUP 1602624	QC		<0.005	0.3	58.0	0.7	9	<0.1	25.0	7.1	106	0.71	4.0	<0.5	0.2	12	<0.1	<0.1	<0.1	17	0.70
Reference Materials																					
STD DS11	Standard			14.7	159.1	138.9	347	1.5	79.0	14.2	1073	3.20	47.2	58.0	7.9	69	2.7	7.6	12.3	50	1.10
STD DS11	Standard			14.6	164.5	139.2	366	1.8	79.5	14.2	1087	3.18	45.8	125.9	7.9	68	2.6	8.2	12.2	51	1.09
STD OREAS45EA	Standard			1.5	734.0	14.6	33	0.3	422.0	54.6	432	22.75	12.4	60.4	10.6	4	<0.1	0.3	0.3	314	0.03
STD OREAS45EA	Standard			1.7	724.7	14.8	33	0.3	411.3	54.4	423	21.50	12.0	57.2	10.3	4	<0.1	0.3	0.3	310	0.03
STD OXC145	Standard		0.216																		
STD OXC145	Standard		0.216																		
STD OXH139	Standard		1.314																		
STD OXN134	Standard		7.679																		
STD OXN134	Standard		7.466																		
STD OXN134 Expected			7.667																		
STD OXC145 Expected			0.212																		
STD OXH139 Expected			1.312																		
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD DS11 Expected				13.9	156	138	345	1.71	81.9	14.2	1055	3.2082	42.8	79	7.65	67.3	2.37	7.2	12.2	50	1.063
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.6	15.1	1.3	46	<0.1	1.7	4.8	631	1.90	4.1	0.5	1.9	30	<0.1	<0.1	<0.1	24	0.77



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 1 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17001090.1

Method Analyte Unit MDL		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1602637	Rock	0.008	1	31	0.27	20	0.091	<20	0.65	0.029	0.01	<0.1	<0.01	2.7	<0.1	<0.05	1	<0.5	<0.2
REP 1602637	QC																		
Core Reject Duplicates																			
1602624	Rock	0.003	<1	24	0.39	16	0.096	<20	0.68	0.048	0.01	<0.1	<0.01	3.0	<0.1	<0.05	1	<0.5	<0.2
DUP 1602624	QC	0.004	<1	24	0.39	19	0.095	<20	0.73	0.046	0.01	<0.1	<0.01	3.1	<0.1	<0.05	1	<0.5	<0.2
Reference Materials																			
STD DS11	Standard	0.078	20	61	0.86	435	0.098	<20	1.22	0.072	0.43	2.4	0.29	3.4	5.0	0.29	5	2.4	4.7
STD DS11	Standard	0.077	19	60	0.87	430	0.096	<20	1.18	0.073	0.42	3.2	0.28	3.2	5.2	0.29	5	2.2	5.0
STD OREAS45EA	Standard	0.031	8	867	0.09	150	0.104	<20	3.65	0.016	0.06	<0.1	<0.01	80.8	<0.1	<0.05	13	1.4	<0.2
STD OREAS45EA	Standard	0.030	7	849	0.09	149	0.100	<20	3.42	0.017	0.06	<0.1	<0.01	81.7	<0.1	<0.05	12	1.6	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH139	Standard																		
STD OXN134	Standard																		
STD OXN134	Standard																		
STD OXN134 Expected																			
STD OXC145 Expected																			
STD OXH139 Expected																			
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD DS11 Expected		0.0701	18.6	61.5	0.85	417	0.0976		1.129	0.0694	0.4	2.9	0.3	3.1	4.9	0.2835	4.7	1.9	4.56
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.045	6	3	0.60	67	0.082	<20	1.13	0.076	0.10	0.4	<0.01	3.1	<0.1	<0.05	4	<0.5	<0.2



BUREAU
VERITAS

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI17001090.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
ROCK-WHI	Prep Blank		<0.005	0.7	16.6	1.4	46	<0.1	2.0	5.2	640	2.00	4.6	1.0	2.0	30	<0.1	<0.1	<0.1	28	0.81



BUREAU
VERITAS

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: WHT
Report Date: November 17, 2017

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI17001090.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
ROCK-WHI	Prep Blank	0.043	6	4	0.62	55	0.086	<20	1.19	0.082	0.09	<0.1	<0.01	2.8	<0.1	0.05	4	<0.5	<0.2