



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.  
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada  
PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

Submitted By: Jodie Gibson  
Receiving Lab: Canada-Whitehorse  
Received: August 23, 2017  
Report Date: September 18, 2017  
Page: 1 of 2

## CERTIFICATE OF ANALYSIS

WHI17000671.1

### CLIENT JOB INFORMATION

Project: WHT  
Shipment ID: WHT-20170818-002-PROBE  
P.O. Number  
Number of Samples: 25

### SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days  
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.  
Box 70  
Dawson Yukon Y0B 1G0  
Canada

CC: Isaac Fage  
Shawn Ryan  
Greg Dawson

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	25	Crush, split and pulverize 250 g rock to 200 mesh			WHI
FA430	25	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	25	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	25	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	25	Per sample shipping charges for branch shipments			VAN

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.  
\*\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



**BUREAU VERITAS** MINERAL LABORATORIES  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** WHT  
**Report Date:** September 18, 2017

**Page:** 2 of 2

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI17000671.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2	0.01
1602472	Rock	0.82	<0.005	0.9	25.9	8.0	95	0.2	27.7	4.6	72	3.04	17.5	3.1	6.6	15	<0.1	0.2	0.1	31	0.04
1602473	Rock	0.82	<0.005	0.7	30.0	6.8	115	0.1	36.0	7.6	109	3.11	37.4	3.4	6.8	14	<0.1	0.5	0.1	30	0.05
1602474	Rock	1.09	<0.005	1.3	29.0	7.3	93	0.1	23.1	4.2	65	2.70	42.4	2.1	6.2	17	<0.1	0.7	0.1	36	0.05
1602475	Rock	0.26	<0.005	1.3	31.2	7.9	88	0.2	27.6	7.1	143	3.11	48.6	1.3	5.8	18	0.1	0.6	0.1	49	0.11
1602476	Rock	0.12	<0.005	0.3	5.2	4.4	22	0.1	2.6	0.5	105	0.20	2.8	1.9	0.2	277	0.2	1.3	<0.1	17	19.14
1602477	Rock	0.51	<0.005	1.6	22.2	5.5	49	0.2	9.4	1.4	36	1.85	34.7	2.4	4.7	12	<0.1	3.0	0.1	34	0.05
1602478	Rock	1.01	<0.005	2.0	25.0	6.1	102	0.2	21.4	2.1	28	3.29	74.1	1.9	5.9	16	0.1	1.0	0.1	25	0.03
1602479	Rock	0.80	0.006	0.9	42.8	5.4	121	0.2	41.1	7.6	198	3.21	5.9	2.2	6.1	30	0.9	<0.1	<0.1	59	0.14
1602480	Rock	0.68	0.007	1.9	45.8	7.2	94	0.2	29.4	10.2	387	2.66	80.6	5.6	5.2	18	0.4	0.9	0.1	42	0.08
1602481	Rock	0.83	0.008	1.0	38.0	5.6	119	0.1	30.3	6.8	120	2.99	103.7	5.4	6.6	10	0.2	0.5	0.1	23	0.03
1602482	Rock	0.94	<0.005	2.4	23.1	5.6	99	0.1	17.0	3.1	39	2.35	47.7	3.0	3.7	16	0.2	0.5	0.1	20	0.03
1602483	Rock	0.77	0.005	1.8	53.1	6.0	140	0.1	40.1	6.7	72	3.35	19.5	1.7	7.1	14	0.2	0.2	0.1	17	0.03
1602484	Rock	0.95	0.019	4.6	62.6	8.2	72	0.3	13.3	2.4	47	2.87	69.1	11.0	5.8	12	0.4	1.3	0.1	43	0.02
1602485	Rock	0.86	<0.005	1.5	31.0	3.7	21	<0.1	5.3	1.6	39	1.21	34.5	2.3	5.1	8	<0.1	0.4	<0.1	17	<0.01
1602486	Rock	0.90	0.006	3.2	45.5	7.9	116	0.2	27.0	3.7	126	2.74	18.7	4.1	6.4	15	<0.1	0.2	0.1	43	0.06
1602487	Rock	0.70	0.007	2.8	29.2	8.2	97	0.2	24.8	4.1	78	2.45	14.5	3.2	4.2	18	<0.1	0.8	0.2	33	0.03
1602488	Rock	0.80	0.010	0.7	43.4	11.2	140	0.2	20.7	14.4	235	2.54	24.8	7.0	6.6	19	0.2	0.1	0.1	59	0.12
1602489	Rock	0.96	0.010	3.0	49.7	7.4	45	<0.1	13.8	2.1	39	2.04	114.6	8.6	5.8	15	0.4	0.5	0.1	31	0.02
1602490	Rock	0.92	0.011	1.1	50.3	8.1	99	0.2	21.0	15.6	163	2.59	84.8	8.4	6.8	14	0.5	0.2	0.1	40	0.07
1602491	Rock	0.78	0.006	0.6	26.1	9.6	114	0.2	25.9	8.9	144	2.56	22.6	5.0	4.5	16	0.5	0.3	0.2	48	0.09
1602492	Rock	0.92	0.012	0.7	40.6	7.7	178	0.1	31.7	6.7	102	2.57	83.5	13.0	5.4	11	0.1	1.4	0.1	27	0.03
1602493	Rock	0.80	0.014	1.1	70.9	6.9	65	0.1	13.3	1.7	41	2.72	282.1	11.4	4.6	12	0.2	2.0	<0.1	28	0.02
1602494	Rock	0.93	0.011	1.1	35.8	7.2	97	0.1	30.5	5.6	101	3.00	157.3	7.4	5.9	11	<0.1	1.2	0.1	30	0.03
1602495	Rock	0.86	0.011	0.9	32.7	8.0	72	0.1	24.3	3.3	42	1.95	222.4	7.9	5.7	23	<0.1	0.6	0.1	15	0.03
1602496	Rock	0.80	0.028	0.9	66.4	9.4	185	0.1	56.7	10.6	109	4.88	827.4	25.3	4.4	14	0.5	1.5	<0.1	22	0.04



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** WHT  
**Report Date:** September 18, 2017

**Page:** 2 of 2

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI17000671.1

	Method	Analyte	Unit																	
			AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
			P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
			%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2		
1602472	Rock	0.039	18	25	0.22	332	0.026	<20	0.68	0.012	0.35	<0.1	0.03	3.2	0.5	0.08	2	<0.5	<0.2	
1602473	Rock	0.042	19	26	0.32	267	0.030	<20	0.77	0.013	0.38	<0.1	0.01	3.2	0.4	0.09	2	<0.5	<0.2	
1602474	Rock	0.038	19	26	0.30	275	0.026	<20	0.81	0.015	0.33	<0.1	<0.01	3.5	0.4	0.13	3	0.6	<0.2	
1602475	Rock	0.035	18	33	0.43	250	0.048	<20	1.45	0.019	0.25	<0.1	<0.01	3.5	0.4	0.09	4	<0.5	<0.2	
1602476	Rock	0.014	1	3	11.21	18	0.002	<20	0.10	0.002	0.02	0.2	<0.01	0.4	<0.1	<0.05	<1	<0.5	<0.2	
1602477	Rock	0.044	13	17	0.12	278	0.013	<20	0.48	0.009	0.22	<0.1	<0.01	2.2	0.4	0.10	2	0.5	<0.2	
1602478	Rock	0.052	17	14	0.02	239	0.002	<20	0.30	0.006	0.15	<0.1	0.08	2.6	0.2	<0.05	<1	0.7	<0.2	
1602479	Rock	0.057	16	58	0.83	1194	0.073	<20	1.57	0.008	0.66	<0.1	0.02	5.6	0.5	0.07	4	<0.5	<0.2	
1602480	Rock	0.045	13	30	0.33	495	0.023	<20	0.86	0.007	0.28	<0.1	0.05	6.1	0.4	<0.05	2	0.6	<0.2	
1602481	Rock	0.041	20	17	0.08	231	0.006	<20	0.48	0.007	0.20	<0.1	0.03	3.2	0.2	<0.05	1	<0.5	<0.2	
1602482	Rock	0.028	8	9	0.01	233	<0.001	<20	0.27	0.006	0.13	<0.1	0.10	2.4	0.1	<0.05	<1	0.7	<0.2	
1602483	Rock	0.040	21	10	0.02	238	0.001	<20	0.35	0.008	0.18	<0.1	0.03	2.9	0.2	<0.05	<1	0.9	<0.2	
1602484	Rock	0.064	16	15	0.06	300	0.006	<20	0.42	0.005	0.19	<0.1	0.06	3.1	0.2	0.09	1	1.0	<0.2	
1602485	Rock	0.022	15	11	0.01	134	0.002	<20	0.26	0.007	0.12	<0.1	0.01	1.9	<0.1	<0.05	<1	0.6	<0.2	
1602486	Rock	0.048	17	22	0.28	538	0.027	<20	0.87	0.008	0.33	<0.1	0.02	4.3	0.3	0.11	3	0.7	<0.2	
1602487	Rock	0.040	12	15	0.15	368	0.015	<20	0.56	0.007	0.27	<0.1	0.03	3.2	0.3	0.09	2	0.6	<0.2	
1602488	Rock	0.040	19	44	0.93	730	0.092	<20	1.98	0.006	0.75	<0.1	0.03	7.8	0.5	<0.05	5	<0.5	<0.2	
1602489	Rock	0.038	12	15	0.06	212	0.005	<20	0.42	0.007	0.17	<0.1	0.03	3.0	0.2	<0.05	1	1.5	<0.2	
1602490	Rock	0.044	16	38	0.62	483	0.054	<20	1.28	0.006	0.50	<0.1	0.02	5.1	0.6	<0.05	4	<0.5	<0.2	
1602491	Rock	0.048	10	34	0.75	586	0.067	<20	1.39	0.005	0.68	<0.1	0.03	7.3	0.5	<0.05	4	0.6	<0.2	
1602492	Rock	0.036	12	20	0.22	303	0.023	<20	0.70	0.005	0.27	<0.1	0.03	4.5	0.4	0.06	2	<0.5	<0.2	
1602493	Rock	0.046	9	15	0.01	160	0.001	<20	0.34	0.005	0.12	<0.1	0.10	4.6	0.3	<0.05	1	<0.5	<0.2	
1602494	Rock	0.035	14	19	0.11	318	0.010	<20	0.52	0.005	0.20	<0.1	0.05	4.3	0.3	0.06	2	0.8	<0.2	
1602495	Rock	0.031	21	9	0.03	206	0.001	<20	0.37	0.007	0.18	<0.1	0.04	3.9	0.2	0.09	<1	<0.5	<0.2	
1602496	Rock	0.046	14	11	0.02	220	<0.001	<20	0.45	0.003	0.17	<0.1	0.09	5.6	0.3	<0.05	1	<0.5	<0.2	



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** WHT  
**Report Date:** September 18, 2017

**Page:** 1 of 1

**Part:** 1 of 2

## QUALITY CONTROL REPORT

WHI17000671.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	2
Pulp Duplicates																					
1602482	Rock	0.94	<0.005	2.4	23.1	5.6	99	0.1	17.0	3.1	39	2.35	47.7	3.0	3.7	16	0.2	0.5	0.1	20	0.03
REP 1602482	QC			2.8	24.0	5.8	99	0.1	16.7	3.2	39	2.33	48.8	1.4	3.9	16	0.2	0.5	0.1	19	0.03
Core Reject Duplicates																					
1602479	Rock	0.80	0.006	0.9	42.8	5.4	121	0.2	41.1	7.6	198	3.21	5.9	2.2	6.1	30	0.9	<0.1	<0.1	59	0.14
DUP 1602479	QC		0.006	0.8	41.0	5.2	116	0.2	40.7	7.6	196	3.14	5.8	3.5	6.2	31	0.8	<0.1	<0.1	58	0.14
Reference Materials																					
STD DS11	Standard			12.3	137.1	128.5	319	1.6	74.2	12.5	989	2.88	39.6	104.5	7.0	64	2.1	7.5	11.3	47	0.96
STD OREAS45EA	Standard			1.4	676.1	13.3	30	0.2	384.3	49.2	403	20.66	10.7	53.4	9.9	4	<0.1	0.2	0.2	302	0.03
STD OXC145	Standard		0.214																		
STD OXC145	Standard		0.212																		
STD OXH139	Standard		1.308																		
STD OXH139	Standard		1.307																		
STD OXN117	Standard		7.837																		
STD OXN117	Standard		7.643																		
STD OXN117 Expected			7.679																		
STD OXC145 Expected			0.212																		
STD OXH139 Expected			1.312																		
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	23.51	10.3	53	10.7	3.5	0.03	0.32	0.26	303	0.036
STD DS11 Expected				13.9	156	138	345	1.71	81.9	14.2	1055	3.2082	42.8	79	7.65	67.3	2.37	7.2	12.2	50	1.063
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.7	4.4	2.3	36	<0.1	1.0	3.4	530	1.69	<0.5	0.5	2.2	19	<0.1	<0.1	<0.1	23	0.52
ROCK-WHI	Prep Blank		<0.005	0.6	4.4	2.0	34	<0.1	0.9	3.3	501	1.62	0.5	<0.5	2.3	18	<0.1	<0.1	<0.1	22	0.49



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** WHT  
**Report Date:** September 18, 2017

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Page: 1 of 1

Part: 2 of 2

## QUALITY CONTROL REPORT

WHI17000671.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1602482	Rock	0.028	8	9	0.01	233	<0.001	<20	0.27	0.006	0.13	<0.1	0.10	2.4	0.1	<0.05	<1	0.7	<0.2
REP 1602482	QC	0.030	9	9	0.01	240	<0.001	<20	0.26	0.006	0.13	<0.1	0.10	2.5	0.1	<0.05	<1	0.5	<0.2
Core Reject Duplicates																			
1602479	Rock	0.057	16	58	0.83	1194	0.073	<20	1.57	0.008	0.66	<0.1	0.02	5.6	0.5	0.07	4	<0.5	<0.2
DUP 1602479	QC	0.055	16	57	0.83	1168	0.072	<20	1.57	0.008	0.67	<0.1	0.02	5.4	0.4	0.07	4	0.7	<0.2
Reference Materials																			
STD DS11	Standard	0.068	16	55	0.79	411	0.086	<20	1.07	0.068	0.39	2.8	0.25	3.1	4.6	0.28	5	1.7	4.1
STD OREAS45EA	Standard	0.027	7	783	0.09	136	0.096	<20	3.07	0.021	0.06	<0.1	0.01	81.5	<0.1	<0.05	13	1.2	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH139	Standard																		
STD OXH139	Standard																		
STD OXN117	Standard																		
STD OXN117	Standard																		
STD OXN117 Expected																			
STD OXC145 Expected																			
STD OXH139 Expected																			
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.13	0.02	0.053			78	0.072	0.036	12.4	0.78	0.07
STD DS11 Expected		0.0701	18.6	61.5	0.85	417	0.0976		1.129	0.0694	0.4	2.9	0.3	3.1	4.9	0.2835	4.7	1.9	4.56
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.039	5	2	0.47	60	0.072	<20	0.87	0.077	0.09	<0.1	<0.01	2.9	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.038	6	2	0.44	49	0.072	<20	0.77	0.066	0.08	0.1	<0.01	2.6	<0.1	<0.05	3	<0.5	<0.2