



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Submitted By: Greg Dawson

Receiving Lab: Canada-Whitehorse

Received: June 25, 2018

Report Date: July 12, 2018

Page: 1 of 5

CERTIFICATE OF ANALYSIS

WHI18000130.1

CLIENT JOB INFORMATION

Project: BZA
Shipment ID: BZA180618-02RAB
P.O. Number
Number of Samples: 111

SAMPLE DISPOSAL

RTRN-PLP Return After 90 days
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.
Box 70
Dawson Yukon Y0B 1G0
Canada

CC: Jodie Gibson
Ben McGrath
Wes Hodson
Isaac Fage

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	107	Crush, split and pulverize 250 g rock to 200 mesh			WHI
SLBHP	4	Sort, label and box pulps			WHI
FA430	111	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	111	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	111	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	111	Per sample shipping charges for branch shipments			VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.
*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 2 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1694137	Rab Sample	3.39	0.005	0.9	4.5	23.2	44	0.1	3.3	1.3	108	0.95	22.7	4.2	10.3	13	0.2	0.3	0.1	3	0.07
1694138	Rab Sample	5.03	<0.005	1.0	2.8	17.4	26	0.1	2.8	1.2	74	0.72	5.6	2.5	4.1	14	0.1	0.2	0.1	1	0.11
1694139	Rab Sample	3.47	<0.005	0.6	2.7	19.7	27	0.1	1.6	1.0	99	0.91	14.6	2.4	10.1	12	<0.1	0.2	0.2	<1	0.07
1694140	Rock Pulp	0.08	6.954	8.5	186.3	19.2	71	0.8	13.4	10.9	555	4.67	13.3	8153.3	2.7	69	0.2	5.1	0.5	113	0.96
1694141	Rab Sample	3.26	0.005	0.5	4.3	18.7	32	0.2	1.3	0.9	70	0.69	40.6	3.8	11.1	6	0.2	0.3	0.2	1	0.04
1694142	Rab Sample	3.53	<0.005	0.5	2.9	16.3	31	0.2	1.4	0.8	93	0.92	31.7	2.8	12.2	7	0.1	0.2	0.1	<1	0.04
1694143	Rab Sample	3.23	0.006	0.4	2.4	15.7	24	0.1	1.0	0.7	83	0.75	44.2	2.6	10.8	7	0.1	0.2	<0.1	<1	0.04
1694144	Rab Sample	3.33	0.007	0.6	2.5	16.8	27	0.3	1.3	0.9	81	0.91	73.3	4.9	13.7	5	0.1	0.3	0.1	<1	0.03
1694145	Rab Sample	2.83	0.012	0.5	2.3	17.6	27	0.5	1.0	0.7	70	0.79	81.9	10.2	12.7	8	0.1	0.4	0.1	<1	0.04
1694146	Rab Sample	3.84	0.007	0.5	3.4	17.8	28	0.2	1.2	0.8	109	0.95	45.5	3.3	11.0	13	0.2	0.2	0.1	<1	0.07
1694147	Rab Sample	3.23	0.005	0.5	2.6	19.0	32	0.4	1.0	0.6	89	0.80	71.2	3.8	10.2	9	0.2	0.4	0.1	<1	0.06
1694148	Rab Sample	3.54	0.016	0.5	2.2	16.5	28	0.8	1.0	0.7	107	0.97	66.4	10.2	12.8	9	<0.1	0.2	0.2	<1	0.05
1694149	Rab Sample	3.30	0.013	0.6	3.2	20.0	27	1.3	1.1	0.8	109	0.80	54.4	11.8	9.7	13	0.1	0.2	0.2	<1	0.07
1694150	Rab Sample	3.65	<0.005	0.7	2.4	18.2	30	1.1	1.2	0.9	126	0.99	44.0	3.8	11.0	21	<0.1	0.3	0.1	<1	0.09
1694151	Rab Sample	2.96	<0.005	0.8	3.1	17.8	29	0.3	1.2	0.9	125	1.04	39.8	1.2	10.0	16	0.2	0.4	0.1	<1	0.08
1694152	Rab Sample	3.69	0.007	0.6	2.9	18.4	29	0.3	1.2	0.9	106	0.97	74.2	5.0	12.3	8	0.2	0.7	0.2	<1	0.05
1694153	Rab Sample	3.36	0.008	0.7	3.2	16.9	28	0.6	1.2	0.8	94	0.92	79.7	5.2	13.1	8	0.1	0.5	0.2	<1	0.04
1694154	Rab Sample	3.55	0.005	0.7	2.9	17.2	24	0.4	1.2	0.8	152	0.88	89.1	3.9	13.2	16	0.1	0.7	0.1	<1	0.08
1694155	Rab Sample	3.64	<0.005	0.8	2.8	18.4	25	<0.1	1.3	0.8	92	0.80	30.0	<0.5	11.0	23	0.1	0.2	0.1	<1	0.11
1694156	Rab Sample	3.38	0.009	0.8	3.0	18.9	28	0.2	1.2	0.8	91	0.83	56.2	7.2	11.0	14	<0.1	0.5	0.2	<1	0.07
1694157	Rab Sample	3.37	0.016	0.6	2.3	18.6	26	0.4	1.1	0.8	104	0.90	157.3	13.3	14.5	7	<0.1	0.6	0.1	<1	0.03
1694158	Rab Sample	3.38	0.010	0.5	3.2	18.7	26	1.0	1.1	0.8	112	0.96	97.1	9.7	14.2	8	<0.1	0.4	<0.1	<1	0.03
1694159	Rab Sample	2.89	<0.005	0.7	3.2	19.2	25	0.3	1.2	0.7	91	0.85	81.0	<0.5	14.3	10	<0.1	0.9	0.1	<1	0.04
1694160	Rock Pulp	0.08	7.306	9.4	200.3	20.8	78	1.0	14.2	12.0	596	5.04	14.8	9192.2	2.9	80	0.2	5.2	0.6	121	1.02
1694161	Rab Sample	3.39	<0.005	0.8	2.3	16.4	27	0.3	1.4	0.9	98	1.09	50.1	2.4	14.4	8	<0.1	0.4	0.2	<1	0.04
1694162	Rab Sample	3.73	0.005	0.8	2.8	19.1	31	0.1	1.2	0.9	111	0.95	38.7	1.3	14.0	8	<0.1	0.5	0.1	<1	0.05
1694163	Rab Sample	3.65	0.006	0.8	2.9	21.5	31	0.1	1.2	0.9	143	0.97	40.2	4.9	14.0	9	0.1	0.3	0.1	<1	0.04
1694164	Rab Sample	3.50	0.006	0.7	2.4	20.6	29	0.1	1.1	0.7	110	0.91	49.3	1.5	14.4	8	0.1	0.2	<0.1	<1	0.04
1694165	Rab Sample	3.42	<0.005	0.9	2.9	18.2	24	0.2	1.4	0.8	87	0.94	16.3	<0.5	14.0	8	0.1	0.1	<0.1	<1	0.04
1694166	Rab Sample	3.61	<0.005	0.9	2.5	17.9	25	<0.1	1.2	0.8	98	0.93	21.9	<0.5	13.0	8	<0.1	0.2	0.1	<1	0.05



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 2 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1694137	Rab Sample	0.008	42	7	0.08	263	0.020	<20	0.42	0.024	0.27	0.8	0.01	2.8	<0.1	<0.05	2	<0.5	<0.2			
1694138	Rab Sample	0.008	16	5	0.07	230	0.040	<20	0.36	0.025	0.31	3.1	<0.01	2.3	<0.1	<0.05	2	<0.5	<0.2			
1694139	Rab Sample	0.008	21	4	0.07	233	0.014	<20	0.34	0.027	0.27	1.8	<0.01	3.1	<0.1	<0.05	2	<0.5	<0.2			
1694140	Rock Pulp	0.059	8	18	0.80	117	0.143	<20	1.67	0.181	0.22	4.3	0.20	3.4	<0.1	<0.05	5	<0.5	<0.2			
1694141	Rab Sample	0.008	48	3	0.04	171	0.010	<20	0.26	0.026	0.23	1.3	0.01	2.6	<0.1	<0.05	1	<0.5	<0.2			
1694142	Rab Sample	0.007	28	4	0.06	259	0.005	<20	0.38	0.028	0.30	0.7	0.01	3.1	<0.1	<0.05	2	<0.5	<0.2			
1694143	Rab Sample	0.006	38	3	0.06	202	0.005	<20	0.33	0.021	0.26	0.7	0.02	2.6	<0.1	<0.05	2	<0.5	<0.2			
1694144	Rab Sample	0.006	39	4	0.06	228	0.004	<20	0.38	0.029	0.29	0.6	0.02	2.9	<0.1	<0.05	2	<0.5	<0.2			
1694145	Rab Sample	0.005	47	3	0.06	209	0.005	<20	0.33	0.024	0.25	0.5	0.04	2.5	<0.1	<0.05	2	<0.5	<0.2			
1694146	Rab Sample	0.004	25	4	0.10	285	0.011	<20	0.46	0.027	0.32	0.6	0.02	3.1	<0.1	<0.05	3	<0.5	<0.2			
1694147	Rab Sample	0.004	33	3	0.06	224	0.013	<20	0.35	0.024	0.26	0.4	0.03	2.7	<0.1	<0.05	2	<0.5	<0.2			
1694148	Rab Sample	0.005	45	4	0.09	311	0.004	<20	0.43	0.027	0.31	0.6	0.02	3.1	<0.1	<0.05	2	<0.5	<0.2			
1694149	Rab Sample	0.004	31	4	0.08	295	0.008	<20	0.41	0.028	0.29	0.7	0.02	2.4	<0.1	<0.05	2	<0.5	<0.2			
1694150	Rab Sample	0.006	33	5	0.10	839	0.023	<20	0.46	0.030	0.32	1.1	<0.01	3.7	<0.1	<0.05	3	<0.5	<0.2			
1694151	Rab Sample	0.007	27	5	0.08	578	0.016	<20	0.44	0.029	0.31	1.1	<0.01	3.0	<0.1	<0.05	3	<0.5	<0.2			
1694152	Rab Sample	0.007	39	5	0.08	263	0.006	<20	0.44	0.027	0.32	0.7	0.02	3.3	<0.1	<0.05	2	<0.5	<0.2			
1694153	Rab Sample	0.007	46	5	0.05	243	0.005	<20	0.36	0.029	0.29	0.8	0.02	3.0	<0.1	<0.05	2	<0.5	<0.2			
1694154	Rab Sample	0.007	38	5	0.11	269	0.022	<20	0.43	0.028	0.35	1.0	<0.01	3.6	<0.1	<0.05	2	<0.5	<0.2			
1694155	Rab Sample	0.008	30	5	0.12	243	0.034	<20	0.44	0.030	0.33	1.6	<0.01	4.1	<0.1	<0.05	2	<0.5	<0.2			
1694156	Rab Sample	0.009	33	5	0.07	232	0.018	<20	0.39	0.030	0.28	1.0	0.01	3.3	<0.1	<0.05	2	<0.5	<0.2			
1694157	Rab Sample	0.006	44	4	0.07	226	0.002	<20	0.37	0.026	0.29	0.5	0.01	2.8	<0.1	<0.05	2	<0.5	<0.2			
1694158	Rab Sample	0.006	43	4	0.06	227	0.001	<20	0.37	0.025	0.28	0.4	0.02	2.6	<0.1	<0.05	2	<0.5	<0.2			
1694159	Rab Sample	0.006	44	5	0.07	228	0.001	<20	0.38	0.021	0.29	0.6	0.01	2.6	0.2	<0.05	1	<0.5	<0.2			
1694160	Rock Pulp	0.063	9	19	0.86	135	0.158	<20	1.83	0.196	0.23	5.5	0.23	3.9	<0.1	<0.05	5	<0.5	<0.2			
1694161	Rab Sample	0.006	42	5	0.09	252	0.002	<20	0.44	0.025	0.30	0.8	<0.01	3.9	0.1	<0.05	2	<0.5	<0.2			
1694162	Rab Sample	0.006	42	5	0.10	225	0.003	<20	0.41	0.027	0.29	0.8	<0.01	3.8	<0.1	<0.05	2	<0.5	<0.2			
1694163	Rab Sample	0.006	47	5	0.09	202	0.002	<20	0.37	0.025	0.28	0.6	<0.01	3.5	<0.1	<0.05	2	<0.5	<0.2			
1694164	Rab Sample	0.006	45	5	0.08	197	0.002	<20	0.39	0.028	0.30	0.6	<0.01	3.2	<0.1	<0.05	1	<0.5	<0.2			
1694165	Rab Sample	0.007	34	5	0.10	239	0.003	<20	0.43	0.024	0.31	0.7	0.02	2.6	0.1	<0.05	2	<0.5	<0.2			
1694166	Rab Sample	0.006	36	6	0.11	226	0.003	<20	0.43	0.023	0.31	0.7	<0.01	3.4	<0.1	<0.05	2	<0.5	<0.2			



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: White Gold Corp.
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 3 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1694167	Rab Sample	3.75	<0.005	0.9	3.1	19.3	27	0.2	1.2	0.9	84	0.91	27.7	1.3	11.3	11	<0.1	0.2	0.2	<1	0.06
1694168	Rab Sample	3.53	<0.005	1.2	2.5	17.9	24	0.2	1.2	0.9	94	0.95	27.9	0.8	12.4	12	<0.1	0.4	<0.1	<1	0.07
1694169	Rab Sample	3.65	0.005	0.7	2.3	18.3	26	<0.1	1.1	0.7	98	0.86	32.0	1.9	13.9	8	<0.1	0.2	0.1	<1	0.05
1694170	Rab Sample	3.11	<0.005	1.0	2.4	20.1	26	0.1	1.1	0.8	99	1.10	20.5	4.1	14.6	13	<0.1	0.3	0.1	<1	0.06
1694171	Rab Sample	3.90	<0.005	1.1	1.7	18.8	25	0.1	1.1	0.9	114	1.10	37.4	4.7	14.8	11	<0.1	0.4	<0.1	<1	0.06
1694172	Rab Sample	3.63	<0.005	1.1	2.9	19.3	27	0.1	1.3	0.8	109	1.04	34.4	5.5	14.8	9	<0.1	0.4	0.2	<1	0.05
1694173	Rab Sample	3.19	<0.005	1.2	3.0	19.7	37	0.4	1.2	1.2	116	0.89	30.1	2.4	14.5	8	0.1	0.6	0.4	<1	0.03
1694174	Rab Sample	3.76	0.006	1.2	5.6	16.9	44	0.4	1.2	0.7	65	0.95	60.3	7.7	15.2	7	0.2	0.3	0.4	<1	0.03
1694175	Rab Sample	3.73	<0.005	1.1	3.9	18.8	40	0.3	1.0	0.4	47	0.88	100.9	3.6	14.9	6	0.3	0.4	0.2	<1	0.02
1694176	Rab Sample	3.80	<0.005	1.3	7.2	18.1	27	0.3	1.3	0.4	34	0.95	92.9	3.2	13.8	7	<0.1	0.6	0.1	<1	<0.01
1694177	Rab Sample	3.57	<0.005	1.0	2.9	30.2	24	0.2	0.8	0.3	27	0.90	234.8	3.4	15.4	4	<0.1	0.5	0.1	<1	0.01
1694178	Rab Sample	3.35	<0.005	1.2	3.1	30.0	26	0.2	1.0	0.3	28	0.98	281.0	2.0	16.8	4	<0.1	0.5	<0.1	<1	<0.01
1694179	Rab Sample	3.45	<0.005	1.2	2.5	16.1	11	0.3	1.0	0.3	32	0.74	204.6	1.4	15.7	3	<0.1	0.3	<0.1	<1	<0.01
1694180	Rock	0.77	<0.005	<0.1	0.2	0.4	<1	<0.1	0.3	0.7	80	0.08	<0.5	<0.5	<0.1	74	<0.1	<0.1	<0.1	<1	32.23
1694181	Rab Sample	3.29	<0.005	1.3	3.2	26.1	18	0.3	1.1	0.3	36	1.13	460.6	3.5	15.1	4	0.3	1.9	<0.1	<1	0.02
1694182	Rab Sample	3.21	<0.005	1.4	2.8	23.0	16	0.2	1.1	0.3	33	0.85	224.1	1.9	13.4	6	0.1	1.2	0.1	<1	0.03
1694183	Rab Sample	3.37	<0.005	1.4	3.5	28.1	13	0.5	1.1	0.3	32	0.74	126.8	1.2	14.9	6	<0.1	0.7	0.1	<1	0.02
1694184	Rab Sample	3.40	0.006	1.3	3.3	39.3	9	0.7	1.1	0.3	31	0.58	164.8	3.9	13.9	5	<0.1	1.4	<0.1	<1	0.02
1694185	Rab Sample	3.64	0.006	1.4	4.2	22.5	9	0.8	1.0	0.3	32	0.52	134.9	3.6	11.8	4	<0.1	1.3	<0.1	<1	0.01
1694186	Rab Sample	3.13	0.035	1.7	10.5	249.0	16	9.5	1.3	0.3	43	0.77	761.7	30.3	14.4	7	0.2	6.3	0.2	<1	0.03
1694187	Rab Sample	2.13	0.335	1.6	45.8	491.1	61	32.8	0.7	0.2	19	1.53	>10000	329.2	25.9	11	0.6	21.0	0.3	<1	0.04
1694188	Rab Sample	2.39	0.097	1.8	16.5	108.2	19	8.2	1.2	0.3	36	1.04	3633.6	104.8	18.4	7	0.3	7.0	0.1	<1	0.02
1694189	Rab Sample	3.30	0.011	1.6	5.4	44.6	9	2.7	1.1	0.4	33	0.57	257.1	24.2	10.1	15	<0.1	1.1	<0.1	<1	0.01
1694190	Rab Sample	3.18	0.006	1.8	8.0	38.5	8	2.8	1.4	0.4	37	0.93	212.1	3.5	12.3	9	<0.1	1.1	<0.1	<1	0.02
1694191	Rab Sample	3.05	0.011	5.2	7.3	28.2	13	1.7	1.2	0.4	31	0.88	346.7	8.0	15.1	13	0.2	2.2	0.2	<1	0.01
1694192	Rab Sample	3.38	0.007	2.3	6.5	25.0	18	0.7	1.1	0.3	35	0.76	131.8	5.9	14.8	11	<0.1	0.6	0.3	<1	0.03
1694193	Rab Sample	2.96	<0.005	1.5	4.0	20.4	21	1.0	1.0	0.7	129	0.76	35.3	1.7	12.1	41	0.4	0.4	0.3	<1	0.45
1694194	Rab Sample	3.78	<0.005	1.6	2.6	10.6	10	0.2	0.9	0.7	67	0.55	22.2	1.2	8.1	49	0.2	0.4	0.1	<1	0.48
1694195	Rab Sample	3.71	<0.005	3.1	6.9	16.9	12	0.3	1.1	0.7	77	0.66	24.1	<0.5	10.2	67	0.3	0.4	0.2	<1	0.77
1694196	Rab Sample	3.33	<0.005	1.6	4.1	14.0	10	0.4	0.9	0.7	67	0.54	19.9	<0.5	6.9	51	0.2	0.6	0.1	<1	0.52



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 3 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.1	0.05	1	0.5
1694167	Rab Sample	0.005	30	5	0.07	200	0.012	<20	0.39	0.030	0.29	0.8	0.01	3.0	<0.1	<0.05	2	<0.5	<0.2			
1694168	Rab Sample	0.006	37	7	0.06	188	0.024	<20	0.36	0.030	0.29	1.4	0.01	3.8	<0.1	<0.05	2	<0.5	<0.2			
1694169	Rab Sample	0.007	56	5	0.10	192	0.004	<20	0.41	0.026	0.30	0.6	0.02	3.6	<0.1	<0.05	2	<0.5	<0.2			
1694170	Rab Sample	0.006	27	5	0.12	298	0.011	<20	0.46	0.023	0.29	1.8	0.02	3.8	<0.1	<0.05	3	<0.5	<0.2			
1694171	Rab Sample	0.005	46	6	0.09	236	0.013	<20	0.43	0.028	0.29	1.2	0.02	3.7	<0.1	<0.05	2	<0.5	<0.2			
1694172	Rab Sample	0.006	44	6	0.11	208	0.009	<20	0.46	0.031	0.30	0.9	0.01	4.0	<0.1	<0.05	2	<0.5	<0.2			
1694173	Rab Sample	0.007	48	6	0.07	267	0.008	<20	0.40	0.027	0.29	1.0	0.02	4.1	<0.1	<0.05	2	<0.5	<0.2			
1694174	Rab Sample	0.005	54	6	0.10	186	0.003	<20	0.44	0.027	0.29	0.9	<0.01	2.8	<0.1	<0.05	2	<0.5	<0.2			
1694175	Rab Sample	0.005	46	6	0.06	185	0.003	<20	0.42	0.029	0.28	0.7	0.01	2.9	0.2	<0.05	2	<0.5	<0.2			
1694176	Rab Sample	0.004	33	6	0.03	553	0.002	<20	0.37	0.031	0.30	1.2	0.01	2.3	0.1	<0.05	1	<0.5	<0.2			
1694177	Rab Sample	0.006	42	6	0.03	170	0.002	<20	0.38	0.027	0.25	0.8	<0.01	2.7	<0.1	<0.05	1	<0.5	<0.2			
1694178	Rab Sample	0.006	41	6	0.03	168	0.002	<20	0.36	0.026	0.25	0.7	0.01	2.4	<0.1	<0.05	1	<0.5	<0.2			
1694179	Rab Sample	0.004	24	6	0.02	166	0.003	<20	0.39	0.029	0.26	0.8	<0.01	2.1	<0.1	<0.05	2	<0.5	<0.2			
1694180	Rock	0.005	1	<1	0.44	13	0.001	<20	0.02	0.002	<0.01	<0.1	<0.01	0.1	<0.1	<0.05	<1	<0.5	<0.2			
1694181	Rab Sample	0.007	45	7	0.03	208	0.002	<20	0.43	0.036	0.32	0.9	0.02	3.9	<0.1	<0.05	2	<0.5	<0.2			
1694182	Rab Sample	0.004	53	7	0.03	202	0.002	<20	0.32	0.026	0.27	1.1	0.02	2.3	<0.1	<0.05	1	<0.5	<0.2			
1694183	Rab Sample	0.005	41	8	0.04	264	0.002	<20	0.35	0.030	0.29	1.4	0.03	2.7	0.1	<0.05	2	<0.5	<0.2			
1694184	Rab Sample	0.006	50	6	0.03	235	0.001	<20	0.33	0.024	0.32	1.1	0.04	1.8	0.1	0.06	1	<0.5	<0.2			
1694185	Rab Sample	0.004	38	7	0.02	251	0.002	<20	0.27	0.028	0.32	1.5	0.03	1.0	0.1	<0.05	1	<0.5	<0.2			
1694186	Rab Sample	0.006	51	7	0.04	404	<0.001	<20	0.37	0.017	0.39	1.5	0.08	1.6	0.1	0.11	1	<0.5	<0.2			
1694187	Rab Sample	0.009	88	3	0.03	848	<0.001	<20	0.47	0.004	0.42	0.3	0.10	3.9	0.2	0.11	1	<0.5	<0.2			
1694188	Rab Sample	0.007	56	6	0.02	685	<0.001	<20	0.33	0.006	0.34	1.0	0.05	2.2	0.1	<0.05	<1	<0.5	<0.2			
1694189	Rab Sample	0.006	36	9	0.01	4005	0.001	<20	0.28	0.021	0.32	2.3	0.04	0.9	0.1	0.13	<1	<0.5	<0.2			
1694190	Rab Sample	0.005	39	9	0.02	1996	0.001	<20	0.31	0.025	0.34	2.8	0.04	1.4	0.1	0.11	1	<0.5	<0.2			
1694191	Rab Sample	0.005	33	9	0.02	1704	0.001	<20	0.32	0.024	0.37	3.2	0.04	1.6	0.1	0.13	1	<0.5	<0.2			
1694192	Rab Sample	0.005	39	6	0.04	699	<0.001	<20	0.40	0.014	0.31	0.7	0.09	1.4	0.1	0.06	1	<0.5	<0.2			
1694193	Rab Sample	0.005	26	7	0.02	429	0.002	<20	0.38	0.035	0.23	1.6	0.02	2.3	0.1	<0.05	1	<0.5	<0.2			
1694194	Rab Sample	0.005	22	8	0.02	327	0.011	<20	0.39	0.042	0.24	4.3	<0.01	1.8	0.1	<0.05	2	<0.5	<0.2			
1694195	Rab Sample	0.005	29	8	0.03	326	0.005	<20	0.42	0.023	0.29	3.1	<0.01	2.1	<0.1	0.05	2	<0.5	<0.2			
1694196	Rab Sample	0.005	18	8	0.02	312	0.012	<20	0.41	0.029	0.23	3.8	0.01	1.6	<0.1	<0.05	2	<0.5	<0.2			



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 4 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1694197	Rab Sample	3.44	<0.005	1.7	2.8	16.5	9	0.2	1.0	0.6	89	0.73	14.0	<0.5	11.5	90	0.3	0.5	0.1	<1	1.01
1694198	Rab Sample	3.65	0.025	1.8	2.9	23.9	11	0.4	0.9	0.6	101	0.75	26.7	5.2	14.5	128	0.4	0.2	0.2	<1	1.40
1694199	Rab Sample	3.68	0.019	1.0	4.7	41.3	15	0.6	0.7	0.7	131	0.93	47.9	26.7	18.9	254	0.9	0.2	0.3	<1	2.33
1694200	Rock Pulp	0.09	7.378	8.8	184.7	19.3	72	0.8	12.3	10.7	583	4.68	14.2	7793.1	2.9	74	0.2	4.5	0.6	116	1.01
1694201	Rab Sample	3.76	0.033	2.0	7.4	58.9	25	0.7	0.3	0.6	292	1.05	146.9	29.8	21.3	586	1.2	0.2	0.3	<1	5.65
1694202	Rab Sample	3.75	0.059	1.9	4.4	31.8	25	0.5	0.6	0.6	271	1.12	153.8	50.9	20.9	296	0.7	0.2	0.2	<1	3.08
1694203	Rab Sample	3.34	0.006	1.0	4.7	40.2	20	0.3	0.5	0.5	254	0.91	23.3	2.0	19.0	315	0.6	0.1	0.2	<1	3.39
1694204	Rab Sample	3.57	0.010	1.3	1.6	17.7	20	0.2	0.2	0.5	145	0.80	106.4	10.0	22.8	291	0.5	0.4	0.3	<1	2.99
1694205	Rab Sample	2.97	0.027	0.6	5.5	30.6	18	0.5	0.1	0.6	144	0.64	437.7	21.2	22.8	440	0.7	0.6	0.4	<1	4.92
1694206	Rab Sample	3.44	0.025	1.1	6.3	28.1	19	0.5	0.7	0.7	122	0.83	63.0	13.8	18.5	170	0.6	0.4	0.2	<1	2.21
1694207	Rab Sample	4.62	<0.005	1.3	23.8	8.7	68	0.3	13.3	8.5	259	1.65	15.0	2.0	2.4	24	0.3	1.5	0.1	12	0.40
1694208	Rab Sample	3.74	<0.005	0.7	16.3	9.0	47	0.2	10.4	5.5	205	1.37	10.6	3.3	2.2	29	0.2	0.7	0.1	10	0.43
1694209	Rab Sample	5.66	<0.005	0.6	20.3	10.5	49	0.2	14.4	6.8	200	1.41	16.6	<0.5	2.6	35	0.2	1.0	0.1	12	0.48
1694210	Rab Sample	4.13	<0.005	0.9	17.9	8.8	66	0.2	12.2	5.6	273	1.53	12.1	<0.5	2.1	25	0.3	1.0	0.1	12	0.40
1694211	Rab Sample	4.24	<0.005	1.3	23.9	7.8	61	0.2	17.9	9.0	259	1.45	15.7	<0.5	2.2	39	0.4	1.9	0.1	14	0.51
1694212	Rab Sample	4.45	<0.005	0.9	15.9	13.3	57	0.2	24.7	11.8	251	1.45	12.8	<0.5	2.2	28	0.2	1.0	0.2	11	0.36
1694213	Rab Sample	4.81	<0.005	0.6	18.3	12.0	42	0.2	7.4	4.1	187	1.57	7.2	<0.5	2.6	28	0.2	1.3	0.2	13	0.33
1694214	Rab Sample	2.08	<0.005	0.7	19.7	15.3	45	0.3	18.7	8.8	270	1.41	76.6	<0.5	2.5	26	0.3	1.5	0.2	10	0.37
1694215	Rab Sample	4.04	<0.005	0.9	26.9	13.2	47	0.4	12.4	5.8	183	1.44	109.9	1.8	2.7	26	0.6	1.4	0.2	12	0.30
1694216	Rab Sample	3.05	<0.005	0.7	23.7	15.6	46	0.4	18.8	8.8	328	1.29	44.3	<0.5	2.8	28	0.6	1.0	0.2	9	0.35
1694217	Rab Sample	4.14	<0.005	0.7	22.1	18.3	35	0.4	22.1	9.0	205	1.35	4.0	<0.5	3.7	29	0.3	0.8	0.3	10	0.37
1694218	Rab Sample	3.91	<0.005	1.0	22.5	16.4	41	0.4	16.2	11.1	273	1.47	4.7	<0.5	3.6	17	0.6	0.8	0.2	9	0.30
1694219	Rab Sample	4.47	0.019	0.9	23.9	29.3	53	0.8	21.6	9.4	319	1.64	70.9	5.8	2.7	27	0.5	1.1	0.5	12	0.31
1694220	Rock Pulp	0.09	6.958	9.7	192.0	20.3	76	0.8	13.3	11.6	605	5.01	15.2	7440.0	2.9	76	0.2	5.2	0.6	121	1.02
1694221	Rab Sample	3.63	0.009	1.5	41.7	18.7	56	1.1	17.8	5.2	236	1.76	33.1	5.3	3.8	29	0.8	1.3	0.3	11	0.17
1694222	Rab Sample	3.63	0.021	1.4	50.6	12.4	72	1.0	27.2	11.8	300	2.00	188.9	8.7	4.4	26	1.1	1.8	0.3	12	0.25
1694223	Rab Sample	3.14	0.010	1.2	53.8	22.6	97	1.0	39.7	24.9	564	2.42	93.6	5.3	5.7	28	1.4	1.7	0.4	17	0.28
1694224	Rab Sample	3.33	0.048	1.2	61.0	14.4	118	1.0	26.6	13.5	415	2.41	32.4	24.7	7.2	29	0.9	1.6	0.2	18	0.21
1694225	Rab Sample	4.15	<0.005	1.5	27.3	36.9	98	1.4	12.8	5.7	347	2.74	3.0	0.5	6.7	26	0.4	1.7	0.3	13	0.27
1694226	Rab Sample	3.92	<0.005	1.2	44.0	16.8	138	0.6	32.5	18.7	571	2.52	30.8	<0.5	7.5	39	1.4	1.5	0.2	16	0.70



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 4 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1694197	Rab Sample	0.005	33	8	0.03	1238	0.006	<20	0.47	0.026	0.29	2.2	<0.01	2.4	0.1	<0.05	2	<0.5	<0.2
1694198	Rab Sample	0.005	43	7	0.04	2358	<0.001	<20	0.41	0.009	0.29	0.9	0.05	3.4	0.1	0.05	1	<0.5	<0.2
1694199	Rab Sample	0.004	41	5	0.07	306	<0.001	<20	0.49	0.008	0.36	0.6	0.04	5.1	0.1	0.27	1	<0.5	<0.2
1694200	Rock Pulp	0.061	8	17	0.84	121	0.139	<20	1.82	0.189	0.22	3.4	0.20	3.4	<0.1	<0.05	5	<0.5	<0.2
1694201	Rab Sample	0.005	43	4	0.07	435	<0.001	<20	0.46	0.010	0.33	0.4	0.03	6.6	0.2	0.39	1	<0.5	<0.2
1694202	Rab Sample	0.005	50	5	0.03	1166	<0.001	<20	0.43	0.018	0.30	0.6	0.05	5.3	0.2	0.13	1	<0.5	<0.2
1694203	Rab Sample	0.004	47	5	0.04	1286	<0.001	<20	0.44	0.016	0.29	0.5	0.04	4.4	0.2	0.09	1	<0.5	<0.2
1694204	Rab Sample	0.006	48	3	0.05	500	<0.001	<20	0.48	0.011	0.36	0.2	0.02	4.4	0.2	0.24	1	<0.5	<0.2
1694205	Rab Sample	0.004	38	2	0.05	237	<0.001	<20	0.36	0.006	0.35	0.1	<0.01	3.1	0.2	0.40	<1	<0.5	<0.2
1694206	Rab Sample	0.005	45	6	0.04	412	<0.001	<20	0.43	0.013	0.35	0.7	0.02	2.9	0.2	0.36	1	<0.5	<0.2
1694207	Rab Sample	0.058	6	17	0.48	285	0.100	<20	1.01	0.022	0.22	1.6	0.24	1.3	0.1	<0.05	3	<0.5	<0.2
1694208	Rab Sample	0.056	5	13	0.39	245	0.107	<20	0.88	0.025	0.24	1.4	0.17	1.1	<0.1	<0.05	3	<0.5	<0.2
1694209	Rab Sample	0.066	5	15	0.43	238	0.119	<20	0.96	0.027	0.27	1.3	0.19	1.3	0.1	<0.05	3	<0.5	<0.2
1694210	Rab Sample	0.058	5	14	0.49	237	0.095	<20	0.97	0.024	0.23	1.8	0.16	1.2	<0.1	<0.05	3	<0.5	<0.2
1694211	Rab Sample	0.059	6	17	0.46	194	0.110	<20	0.95	0.032	0.20	1.4	0.24	1.3	<0.1	<0.05	3	<0.5	<0.2
1694212	Rab Sample	0.057	4	14	0.46	210	0.096	<20	0.86	0.025	0.22	1.9	0.17	1.1	<0.1	<0.05	3	<0.5	<0.2
1694213	Rab Sample	0.060	4	16	0.49	225	0.109	<20	0.92	0.029	0.26	1.2	0.17	1.3	<0.1	<0.05	3	<0.5	<0.2
1694214	Rab Sample	0.067	4	12	0.36	261	0.096	<20	0.79	0.020	0.30	1.1	0.18	1.1	0.1	<0.05	2	<0.5	<0.2
1694215	Rab Sample	0.068	6	13	0.26	275	0.095	<20	0.72	0.020	0.32	0.7	0.22	1.5	0.1	<0.05	2	<0.5	<0.2
1694216	Rab Sample	0.076	5	11	0.23	272	0.092	<20	0.64	0.018	0.32	0.7	0.16	1.4	0.1	<0.05	2	<0.5	<0.2
1694217	Rab Sample	0.079	6	12	0.25	285	0.118	<20	0.69	0.024	0.34	0.6	0.16	1.3	0.1	0.08	2	0.5	<0.2
1694218	Rab Sample	0.064	6	11	0.28	304	0.104	<20	0.71	0.014	0.34	0.5	0.16	1.3	0.1	<0.05	2	<0.5	<0.2
1694219	Rab Sample	0.070	6	15	0.36	281	0.096	<20	0.77	0.014	0.31	1.5	0.31	1.5	0.1	<0.05	2	<0.5	<0.2
1694220	Rock Pulp	0.068	9	19	0.86	130	0.154	<20	1.78	0.194	0.23	5.0	0.21	3.6	<0.1	<0.05	5	<0.5	<0.2
1694221	Rab Sample	0.058	10	13	0.15	257	0.113	<20	0.53	0.014	0.26	0.9	0.54	2.2	0.2	<0.05	2	<0.5	<0.2
1694222	Rab Sample	0.066	12	14	0.27	272	0.094	<20	0.70	0.017	0.29	1.0	0.45	2.2	0.2	<0.05	2	1.3	<0.2
1694223	Rab Sample	0.083	17	21	0.59	253	0.127	<20	1.04	0.017	0.28	1.0	0.51	2.9	0.2	<0.05	3	0.9	<0.2
1694224	Rab Sample	0.081	17	21	0.56	287	0.152	<20	1.17	0.021	0.28	0.1	0.45	3.4	0.2	<0.05	3	1.2	<0.2
1694225	Rab Sample	0.065	13	16	0.62	310	0.170	<20	0.92	0.016	0.26	0.5	0.76	2.1	0.2	0.09	3	0.9	<0.2
1694226	Rab Sample	0.076	22	19	0.67	280	0.149	<20	1.07	0.020	0.28	0.5	0.38	2.3	0.2	0.33	3	0.9	<0.2



BUREAU VERITAS MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 5 of 5

Part: 1 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1694227	Rab Sample	4.18	0.008	0.8	32.2	17.3	63	0.5	27.7	13.6	284	1.67	5.9	3.6	7.6	38	0.9	1.1	0.2	13	0.66
1694228	Rab Sample	4.41	0.047	0.8	31.6	19.7	65	0.6	21.6	13.0	184	1.56	111.7	3.5	8.0	28	1.1	1.4	0.3	13	0.44
1694229	Rab Sample	3.65	0.005	1.3	63.7	11.2	151	0.4	34.8	17.6	385	2.65	186.5	<0.5	7.5	31	2.5	2.7	0.2	25	0.53
1694230	Rab Sample	4.04	0.006	1.3	39.8	13.3	102	0.5	34.2	14.5	436	2.58	393.2	2.3	7.5	67	1.2	3.1	0.2	25	1.29
1694231	Rab Sample	3.13	<0.005	1.2	21.6	17.3	92	1.0	20.1	12.2	572	2.12	21.1	<0.5	7.6	76	1.1	2.5	0.2	19	1.56
1694232	Rab Sample	3.66	0.016	3.7	27.9	19.5	88	3.2	17.6	5.4	288	3.32	18.7	11.8	6.4	171	0.4	2.8	0.2	33	0.19
1694233	Rab Sample	3.72	0.024	5.4	53.1	85.4	182	14.2	11.5	2.6	379	3.35	6.6	15.0	5.5	170	0.2	29.1	0.2	17	0.17
1694234	Rab Sample	3.61	0.055	6.9	138.4	154.1	236	21.4	15.6	8.2	440	3.54	4.3	52.1	4.8	212	1.9	74.4	<0.1	14	0.99
1694235	Rab Sample	3.00	0.031	5.5	49.8	71.7	130	7.8	21.6	11.0	408	3.53	11.6	32.6	5.0	128	0.6	16.1	0.2	33	0.25
1694236	Rab Sample	3.70	0.009	2.0	28.6	13.6	93	0.7	27.7	15.1	558	3.50	13.5	5.2	5.4	79	0.4	2.1	0.2	68	1.28
1694237	Rab Sample	3.51	0.007	1.9	28.5	9.9	85	0.5	26.0	14.4	694	3.25	15.9	5.8	4.7	106	0.4	1.4	0.1	69	1.70
1694238	Rab Sample	2.11	0.008	1.7	26.2	7.3	82	0.4	24.6	14.1	605	3.26	13.9	4.3	4.5	75	0.3	0.9	<0.1	63	1.37
1694239	Rab Sample	2.33	0.005	1.6	29.0	10.2	92	0.4	28.7	15.0	553	3.88	7.0	<0.5	4.5	131	0.6	0.8	<0.1	90	1.96
1694240	Rock	0.56	<0.005	<0.1	1.7	13.7	4	<0.1	0.6	0.7	79	0.07	<0.5	4.7	<0.1	66	<0.1	<0.1	<0.1	1	29.04
1694241	Rab Sample	3.15	0.019	2.2	37.9	47.5	119	2.0	25.3	14.2	458	3.39	13.6	15.8	5.2	94	0.6	2.3	0.2	64	1.01
1694242	Rab Sample	3.11	0.019	2.1	28.5	31.8	46	2.6	15.8	8.4	254	1.69	21.6	14.6	6.7	75	0.4	3.4	<0.1	18	0.87
1694243	Rab Sample	2.92	0.006	1.2	18.7	15.2	25	0.4	9.8	5.1	344	0.85	11.9	4.6	6.7	123	0.3	4.4	<0.1	11	1.69
1694244	Rab Sample	2.75	<0.005	1.3	19.9	17.6	32	0.3	12.7	6.6	235	0.87	9.4	5.0	8.1	46	0.3	4.1	<0.1	10	0.48
1694245	Rab Sample	2.37	0.009	2.7	16.2	19.8	64	0.5	15.6	7.8	485	2.16	5.0	3.6	8.6	60	0.3	2.9	0.1	19	0.68
1694246	Rab Sample	0.75	<0.005	1.9	13.8	13.8	51	0.4	11.7	5.8	431	1.88	7.0	1.7	6.3	65	0.2	2.5	0.1	20	0.73
1694247	Rab Sample	0.51	0.006	3.3	28.4	23.2	73	1.2	22.0	11.0	429	2.20	14.5	7.0	6.6	86	0.5	4.1	0.1	29	0.90



BUREAU MINERAL LABORATORIES
VERITAS Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 5 of 5

Part: 2 of 2

CERTIFICATE OF ANALYSIS

WHI18000130.1

	Method Analyte Unit MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1694227	Rab Sample	0.076	22	14	0.35	314	0.118	<20	0.71	0.021	0.35	0.8	0.20	2.2	0.2	0.35	2	0.7	<0.2
1694228	Rab Sample	0.075	18	13	0.38	266	0.109	<20	0.76	0.014	0.32	1.1	0.14	2.4	0.2	0.17	2	0.9	<0.2
1694229	Rab Sample	0.082	21	21	0.67	299	0.081	<20	1.17	0.013	0.30	0.8	0.09	6.2	0.2	0.09	3	1.6	<0.2
1694230	Rab Sample	0.075	23	24	0.92	237	0.007	<20	1.12	0.016	0.26	0.7	0.11	6.3	0.2	0.34	3	1.3	<0.2
1694231	Rab Sample	0.066	27	20	0.89	301	0.004	<20	1.34	0.015	0.25	0.3	0.30	3.3	0.3	0.24	5	1.3	<0.2
1694232	Rab Sample	0.059	16	44	1.36	348	0.003	<20	1.57	0.059	0.21	0.3	0.45	3.2	0.3	0.33	5	1.2	<0.2
1694233	Rab Sample	0.086	11	24	1.64	563	0.004	<20	1.47	0.042	0.26	0.7	0.87	2.7	0.4	0.48	4	1.3	<0.2
1694234	Rab Sample	0.063	16	16	1.63	503	0.003	<20	1.13	0.011	0.23	0.6	4.23	4.5	0.3	0.95	3	2.1	<0.2
1694235	Rab Sample	0.064	16	40	1.63	402	0.005	<20	1.65	0.018	0.18	0.4	0.84	4.1	0.3	0.25	5	2.0	<0.2
1694236	Rab Sample	0.073	20	68	1.70	210	0.005	<20	1.91	0.022	0.12	0.3	0.65	7.6	0.1	0.12	7	0.7	<0.2
1694237	Rab Sample	0.069	17	64	1.59	220	0.016	<20	1.84	0.021	0.11	0.3	0.56	8.4	0.1	<0.05	7	<0.5	<0.2
1694238	Rab Sample	0.066	16	57	1.62	266	0.011	<20	1.82	0.023	0.13	0.2	0.58	7.9	0.1	0.07	7	0.5	<0.2
1694239	Rab Sample	0.065	17	71	1.99	254	0.006	<20	2.18	0.022	0.09	0.3	0.25	10.9	0.1	0.19	8	0.9	<0.2
1694240	Rock	0.006	1	<1	0.88	11	0.002	<20	0.02	0.004	0.01	0.2	<0.01	0.2	<0.1	<0.05	<1	<0.5	<0.2
1694241	Rab Sample	0.068	18	63	1.76	351	0.010	<20	1.72	0.030	0.19	0.4	0.24	9.9	0.2	0.43	7	1.4	<0.2
1694242	Rab Sample	0.058	18	20	0.37	431	0.005	<20	0.67	0.044	0.34	0.8	0.23	3.3	0.2	0.70	2	0.7	<0.2
1694243	Rab Sample	0.050	19	14	0.17	310	0.004	<20	0.44	0.049	0.23	1.4	0.12	1.6	0.2	0.22	1	<0.5	<0.2
1694244	Rab Sample	0.060	23	12	0.17	445	0.004	<20	0.55	0.037	0.36	0.7	0.14	1.4	0.2	0.05	2	0.6	<0.2
1694245	Rab Sample	0.064	26	17	0.75	484	0.008	<20	0.91	0.030	0.37	0.5	0.18	2.9	0.3	0.13	4	0.7	<0.2
1694246	Rab Sample	0.058	19	17	0.73	435	0.011	<20	0.85	0.037	0.35	0.2	0.13	3.0	0.3	0.20	3	<0.5	<0.2
1694247	Rab Sample	0.063	21	34	0.80	328	0.014	<20	1.01	0.031	0.23	0.6	0.35	4.3	0.2	0.19	4	0.6	<0.2



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

BZA

Report Date:

July 12, 2018

Page:

1 of 2

Part:

1 of 2

QUALITY CONTROL REPORT

WHI18000130.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1
Pulp Duplicates																					
1694150	Rab Sample	3.65	<0.005	0.7	2.4	18.2	30	1.1	1.2	0.9	126	0.99	44.0	3.8	11.0	21	<0.1	0.3	0.1	<1	0.09
REP 1694150	QC			0.7	2.4	18.4	28	1.1	1.3	0.8	126	1.01	43.5	2.9	10.8	21	0.1	0.3	0.1	<1	0.09
1694162	Rab Sample	3.73	0.005	0.8	2.8	19.1	31	0.1	1.2	0.9	111	0.95	38.7	1.3	14.0	8	<0.1	0.5	0.1	<1	0.05
REP 1694162	QC		0.005																		
1694184	Rab Sample	3.40	0.006	1.3	3.3	39.3	9	0.7	1.1	0.3	31	0.58	164.8	3.9	13.9	5	<0.1	1.4	<0.1	<1	0.02
REP 1694184	QC		0.007	1.4	3.1	40.4	10	0.6	1.0	0.2	30	0.57	168.0	5.5	13.7	5	0.1	1.6	<0.1	<1	0.02
1694219	Rab Sample	4.47	0.019	0.9	23.9	29.3	53	0.8	21.6	9.4	319	1.64	70.9	5.8	2.7	27	0.5	1.1	0.5	12	0.31
REP 1694219	QC			0.8	23.4	28.9	51	0.8	20.6	8.9	310	1.62	69.3	6.7	2.7	27	0.5	1.1	0.5	12	0.31
1694235	Rab Sample	3.00	0.031	5.5	49.8	71.7	130	7.8	21.6	11.0	408	3.53	11.6	32.6	5.0	128	0.6	16.1	0.2	33	0.25
REP 1694235	QC		0.029																		
Core Reject Duplicates																					
1694158	Rab Sample	3.38	0.010	0.5	3.2	18.7	26	1.0	1.1	0.8	112	0.96	97.1	9.7	14.2	8	<0.1	0.4	<0.1	<1	0.03
DUP 1694158	QC		0.010	0.5	2.6	18.5	25	1.1	1.2	0.8	108	0.93	95.3	8.3	14.4	8	<0.1	0.4	<0.1	<1	0.03
1694192	Rab Sample	3.38	0.007	2.3	6.5	25.0	18	0.7	1.1	0.3	35	0.76	131.8	5.9	14.8	11	<0.1	0.6	0.3	<1	0.03
DUP 1694192	QC		0.006	2.4	6.1	25.5	18	0.7	1.1	0.3	34	0.76	136.1	6.1	14.7	12	<0.1	0.7	0.3	<1	0.03
1694226	Rab Sample	3.92	<0.005	1.2	44.0	16.8	138	0.6	32.5	18.7	571	2.52	30.8	<0.5	7.5	39	1.4	1.5	0.2	16	0.70
DUP 1694226	QC		<0.005	1.4	43.9	17.3	149	0.7	34.1	20.1	592	2.56	32.6	<0.5	7.5	40	1.3	1.4	0.2	16	0.73
Reference Materials																					
STD DS11	Standard			14.2	147.8	140.1	346	1.5	78.7	13.8	970	3.12	39.5	64.6	8.1	66	2.3	7.6	11.6	49	1.03
STD DS11	Standard			14.2	149.5	137.0	328	1.6	78.3	13.6	1016	3.12	42.3	51.9	7.3	64	2.3	7.2	12.4	50	1.04
STD DS11	Standard			15.8	153.3	139.0	338	1.8	80.0	14.0	992	3.04	42.7	57.7	8.0	65	2.5	8.1	11.4	49	1.04
STD DS11	Standard			15.4	151.7	136.9	336	1.6	78.4	13.8	986	3.09	44.0	60.4	7.5	67	2.7	6.6	12.1	49	1.07
STD OREAS45EA	Standard			1.7	713.2	14.9	32	0.2	385.1	53.1	413	22.36	11.5	49.6	10.9	4	<0.1	0.2	0.3	307	0.03
STD OREAS45EA	Standard			1.7	702.2	14.6	32	0.2	396.1	52.0	416	21.60	11.9	50.9	10.8	4	<0.1	0.2	0.3	304	0.03
STD OREAS45EA	Standard			1.7	730.2	14.4	33	0.2	415.1	52.8	433	21.67	12.0	56.3	10.7	4	<0.1	0.2	0.3	306	0.03
STD OREAS45EA	Standard			1.8	726.7	14.9	32	0.2	421.0	52.8	426	21.65	11.9	57.9	10.8	4	<0.1	0.2	0.3	307	0.03
STD OXC145	Standard		0.209																		
STD OXC145	Standard		0.215																		



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

White Gold Corp.

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

BZA

Report Date:

July 12, 2018

Page:

1 of 2

Part:

2 of 2

QUALITY CONTROL REPORT

WHI18000130.1

		Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																				
1694150	Rab Sample	0.006	33	5	0.10	839	0.023	<20	0.46	0.030	0.32	1.1	<0.01	3.7	<0.1	<0.05	3	<0.5	<0.2	
REP 1694150	QC	0.007	34	5	0.11	860	0.024	<20	0.46	0.031	0.32	1.1	<0.01	3.8	<0.1	<0.05	2	<0.5	<0.2	
1694162	Rab Sample	0.006	42	5	0.10	225	0.003	<20	0.41	0.027	0.29	0.8	<0.01	3.8	<0.1	<0.05	2	<0.5	<0.2	
REP 1694162	QC																			
1694184	Rab Sample	0.006	50	6	0.03	235	0.001	<20	0.33	0.024	0.32	1.1	0.04	1.8	0.1	0.06	1	<0.5	<0.2	
REP 1694184	QC	0.005	53	6	0.03	245	0.001	<20	0.33	0.024	0.31	1.1	0.04	1.9	0.1	0.06	1	<0.5	<0.2	
1694219	Rab Sample	0.070	6	15	0.36	281	0.096	<20	0.77	0.014	0.31	1.5	0.31	1.5	0.1	<0.05	2	<0.5	<0.2	
REP 1694219	QC	0.072	6	14	0.36	275	0.097	<20	0.76	0.015	0.31	1.4	0.30	1.6	0.2	<0.05	2	0.5	<0.2	
1694235	Rab Sample	0.064	16	40	1.63	402	0.005	<20	1.65	0.018	0.18	0.4	0.84	4.1	0.3	0.25	5	2.0	<0.2	
REP 1694235	QC																			
Core Reject Duplicates																				
1694158	Rab Sample	0.006	43	4	0.06	227	0.001	<20	0.37	0.025	0.28	0.4	0.02	2.6	<0.1	<0.05	2	<0.5	<0.2	
DUP 1694158	QC	0.006	41	4	0.05	214	0.001	<20	0.36	0.024	0.27	0.4	0.02	2.6	<0.1	<0.05	1	<0.5	<0.2	
1694192	Rab Sample	0.005	39	6	0.04	699	<0.001	<20	0.40	0.014	0.31	0.7	0.09	1.4	0.1	0.06	1	<0.5	<0.2	
DUP 1694192	QC	0.006	41	6	0.04	687	<0.001	<20	0.39	0.013	0.31	0.8	0.09	1.4	0.1	0.06	1	<0.5	<0.2	
1694226	Rab Sample	0.076	22	19	0.67	280	0.149	<20	1.07	0.020	0.28	0.5	0.38	2.3	0.2	0.33	3	0.9	<0.2	
DUP 1694226	QC	0.083	23	19	0.69	279	0.154	<20	1.08	0.018	0.28	0.5	0.38	2.3	0.2	0.35	3	1.2	<0.2	
Reference Materials																				
STD DS11	Standard	0.069	19	59	0.81	420	0.094	<20	1.13	0.070	0.39	2.3	0.23	3.2	4.9	0.27	5	2.1	4.4	
STD DS11	Standard	0.072	18	60	0.82	421	0.091	<20	1.12	0.068	0.39	3.2	0.23	3.1	4.8	0.29	5	2.2	4.8	
STD DS11	Standard	0.069	19	59	0.83	422	0.094	<20	1.16	0.072	0.40	2.8	0.23	3.1	4.8	0.27	5	2.1	4.6	
STD DS11	Standard	0.079	19	62	0.83	445	0.096	<20	1.19	0.072	0.41	2.8	0.23	3.4	5.0	0.28	5	2.5	4.5	
STD OREAS45EA	Standard	0.030	7	942	0.11	145	0.098	<20	3.58	0.021	0.06	<0.1	0.01	79.2	<0.1	<0.05	13	1.4	<0.2	
STD OREAS45EA	Standard	0.030	7	917	0.10	141	0.104	<20	3.46	0.019	0.06	<0.1	0.01	79.5	<0.1	<0.05	13	1.7	<0.2	
STD OREAS45EA	Standard	0.029	7	942	0.11	140	0.103	<20	3.54	0.018	0.06	<0.1	0.02	77.4	<0.1	<0.05	12	1.6	<0.2	
STD OREAS45EA	Standard	0.031	7	935	0.11	150	0.104	<20	3.51	0.018	0.06	<0.1	0.01	79.6	<0.1	<0.05	13	1.4	<0.2	
STD OXC145	Standard																			
STD OXC145	Standard																			



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 2 of 2

Part: 1 of 2

QUALITY CONTROL REPORT

WHI18000130.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
STD OXC145	Standard		0.199																		
STD OXH139	Standard		1.308																		
STD OXH139	Standard		1.303																		
STD OXH139	Standard		1.324																		
STD OXN134	Standard		7.614																		
STD OXN134	Standard		7.732																		
STD OXN134	Standard		7.618																		
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	22.65	11.4	53	10.7	4.05	0.03	0.32	0.26	303	0.036
STD DS11 Expected				13.9	149	138	345	1.71	77.7	14.2	1055	3.1	42.8	79	7.65	67.3	2.37	7.2	12.2	50	1.063
STD OXN134 Expected			7.667																		
STD OXC145 Expected			0.212																		
STD OXH139 Expected			1.312																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank		<0.005																		
BLK	Blank		<0.005																		
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.9	5.0	2.4	49	<0.1	1.0	4.1	617	1.89	2.8	2.8	2.1	25	<0.1	<0.1	<0.1	22	0.75
ROCK-WHI	Prep Blank		<0.005	1.1	4.2	3.4	49	<0.1	1.2	3.9	566	1.79	3.6	1.9	2.0	24	<0.1	<0.1	<0.1	22	0.68



**BUREAU
VERITAS**

MINERAL LABORATORIES
Canada

www.bureauveritas.com/um

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client: **White Gold Corp.**
Box 70
Dawson Yukon Y0B 1G0 Canada

Project: BZA
Report Date: July 12, 2018

Page: 2 of 2

Part: 2 of 2

QUALITY CONTROL REPORT

WHI18000130.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	
		P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
STD OXC145	Standard																		
STD OXH139	Standard																		
STD OXH139	Standard																		
STD OXH139	Standard																		
STD OXN134	Standard																		
STD OXN134	Standard																		
STD OXN134	Standard																		
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.32	0.02	0.053			78	0.072	0.036	12.4	0.78	0.1
STD DS11 Expected		0.0701	18.6	61.5	0.85	417	0.0976		1.129	0.0694	0.4	2.9	0.26	3.1	4.9	0.2835	4.7	2.2	4.56
STD OXN134 Expected																			
STD OXC145 Expected																			
STD OXH139 Expected																			
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
ROCK-WHI	Prep Blank	0.041	6	3	0.50	64	0.078	<20	1.01	0.085	0.11	0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.044	6	3	0.50	58	0.076	<20	1.01	0.081	0.10	<0.1	<0.01	2.6	<0.1	0.07	4	<0.5	<0.2