



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.  
9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada  
PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

Submitted By: Greg Dawson  
Receiving Lab: Canada-Whitehorse  
Received: July 03, 2018  
Report Date: July 26, 2018  
Page: 1 of 4

## CERTIFICATE OF ANALYSIS

WHI18000211.1

### CLIENT JOB INFORMATION

Project: BZA  
Shipment ID: BZA-180610-08RAB  
P.O. Number  
Number of Samples: 63

### SAMPLE DISPOSAL

RTRN-PLP Return After 90 days  
DISP-RJT Dispose of Reject After 60 days

Bureau Veritas does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ground Truth Exploration Inc.  
Box 70  
Dawson Yukon Y0B 1G0  
Canada

CC: Jodie Gibson  
Ben McGrath  
Wes Hodson  
Isaac Fage

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Procedure Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
PRP70-250	60	Crush, split and pulverize 250 g rock to 200 mesh			WHI
SLBHP	3	Sort, label and box pulps			WHI
FA430	63	Lead Collection Fire - Assay Fusion - AAS Finish	30	Completed	VAN
EN002	63	Environmental disposal charge-Fire assay lead waste			VAN
AQ200	63	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN
SHP01	63	Per sample shipping charges for branch shipments			VAN

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Bureau Veritas assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted.  
\*\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1595001	Rab Sample	4.33	0.020	2.6	4.2	30.1	82	0.2	3.8	1.6	128	1.02	117.0	10.3	14.1	8	0.4	0.6	0.2	5	0.05
1595002	Rab Sample	5.40	0.006	1.7	2.8	23.6	61	0.2	1.6	1.4	96	0.81	51.4	1.6	13.6	5	0.3	0.6	0.3	1	0.04
1595003	Rab Sample	3.08	<0.005	1.6	3.3	20.2	47	0.2	1.5	1.1	123	1.00	37.6	2.7	13.6	6	0.2	0.5	0.2	<1	0.04
1595004	Rab Sample	3.16	0.007	0.7	2.7	19.2	46	0.3	1.2	0.9	147	0.92	35.0	6.0	13.5	6	0.4	0.4	0.2	<1	0.04
1595005	Rab Sample	3.16	0.010	0.8	2.0	19.6	65	0.3	1.5	1.1	214	1.20	54.4	5.9	13.8	8	0.5	0.4	0.2	1	0.05
1595006	Rab Sample	3.31	0.010	0.8	1.8	25.6	80	0.3	1.2	1.1	202	0.92	66.6	8.7	13.3	7	0.7	0.6	0.2	2	0.05
1595007	Rab Sample	2.97	0.010	0.7	1.9	19.7	56	0.2	1.0	0.8	79	0.79	54.8	3.4	12.2	6	0.5	0.3	0.2	1	0.04
1595008	Rab Sample	2.99	0.011	2.8	2.5	27.1	81	0.2	2.5	1.0	131	0.74	47.5	9.7	12.9	6	0.7	0.2	<0.1	1	0.04
1595009	Rab Sample	2.84	<0.005	0.9	2.3	33.2	73	0.2	1.4	1.2	166	0.78	26.9	2.6	14.1	7	0.8	0.2	0.1	<1	0.04
1595010	Rab Sample	2.74	0.005	0.7	2.2	31.7	72	0.1	0.9	1.3	166	0.76	27.7	4.1	13.0	6	0.7	0.1	0.1	<1	0.04
1595011	Rab Sample	2.54	<0.005	0.7	2.1	19.3	30	0.1	0.9	0.4	58	0.71	7.0	1.0	12.4	5	0.1	0.2	<0.1	<1	0.02
1595012	Rab Sample	3.39	<0.005	0.7	1.8	24.1	28	0.2	0.7	1.0	104	0.49	6.3	0.5	12.2	6	0.2	0.1	<0.1	<1	0.03
1595013	Rab Sample	3.61	<0.005	0.9	2.3	28.1	47	0.1	0.9	1.0	145	0.74	20.8	2.6	12.2	6	0.4	0.2	<0.1	<1	0.04
1595014	Rab Sample	2.93	0.007	0.7	2.4	24.7	80	0.2	0.9	1.2	118	0.83	36.5	2.0	14.7	9	0.4	0.2	<0.1	<1	0.05
1595015	Rab Sample	2.93	0.007	0.9	1.9	15.7	52	0.3	1.0	0.6	75	0.72	35.2	4.1	12.9	7	0.4	0.3	<0.1	<1	0.04
1595016	Rab Sample	3.15	0.012	0.7	2.5	13.5	46	0.2	0.9	0.6	42	0.66	100.3	11.2	12.8	6	0.9	0.5	<0.1	<1	0.03
1595017	Rab Sample	3.65	0.032	0.7	4.1	17.1	61	0.3	0.9	0.8	53	0.74	181.0	33.2	14.6	6	1.7	0.9	0.2	2	0.04
1595018	Rab Sample	3.33	0.008	0.7	2.7	22.4	55	0.2	1.1	0.7	68	0.74	47.4	6.2	13.5	5	0.5	0.5	0.2	2	0.03
1595019	Rab Sample	3.25	0.008	0.9	2.8	33.1	48	0.2	1.1	0.9	88	0.74	49.5	5.7	13.3	6	0.4	0.5	0.2	1	0.02
1595020	Rock Pulp	0.08	1.192	5.6	200.9	48.9	284	0.7	99.6	16.7	538	3.10	19.4	1154.3	4.0	92	1.2	1.3	0.4	84	1.80
1595021	Rab Sample	3.13	0.015	0.9	1.9	26.3	38	0.2	0.9	0.5	51	0.63	53.5	11.9	11.9	5	0.3	0.7	<0.1	<1	0.02
1595022	Rab Sample	2.79	0.048	1.1	2.7	25.6	40	0.3	0.9	0.3	42	0.77	345.5	47.8	12.3	5	0.6	1.1	<0.1	<1	0.03
1595023	Rab Sample	2.91	0.009	1.0	1.8	12.4	19	0.2	0.8	0.4	21	0.69	110.6	7.8	12.4	5	0.1	0.4	<0.1	<1	0.02
1595024	Rab Sample	3.40	0.012	1.1	1.4	16.4	29	0.3	1.0	0.5	31	0.76	131.4	10.9	14.5	4	0.2	0.4	<0.1	<1	0.02
1595025	Rab Sample	3.85	0.016	1.1	2.7	21.0	33	0.2	1.0	1.2	77	0.64	185.1	10.7	12.4	5	0.3	0.8	<0.1	<1	0.02
1595026	Rab Sample	3.38	0.060	1.2	1.6	15.4	12	0.2	1.0	0.2	30	0.65	116.8	53.6	12.5	5	<0.1	0.5	<0.1	<1	0.01
1595027	Rab Sample	4.00	0.042	1.2	1.3	19.9	10	0.2	0.9	0.5	22	0.50	127.8	33.4	12.8	9	<0.1	0.6	<0.1	<1	0.02
1595028	Rab Sample	3.62	0.014	1.4	2.5	30.2	47	0.2	0.9	0.4	43	1.03	224.3	8.9	16.0	6	0.2	0.6	0.1	<1	0.02
1595029	Rab Sample	3.68	0.060	1.1	3.5	36.7	69	0.3	1.1	2.8	140	0.59	105.6	49.7	13.2	6	0.8	0.7	0.1	1	0.02
1595030	Rab Sample	2.93	0.067	1.1	3.0	33.5	61	0.3	1.1	2.6	137	0.60	100.3	48.0	12.6	5	0.7	0.6	0.1	1	0.02



**BUREAU VERITAS** MINERAL LABORATORIES  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1595001	Rab Sample	0.009	59	7	0.08	199	0.006	<20	0.44	0.015	0.25	1.0	0.02	2.7	<0.1	<0.05	1	<0.5	<0.2			
1595002	Rab Sample	0.006	35	5	0.07	184	0.003	<20	0.38	0.018	0.27	3.9	0.02	3.0	0.2	<0.05	1	<0.5	<0.2			
1595003	Rab Sample	0.008	56	3	0.07	183	0.012	<20	0.34	0.020	0.25	0.6	<0.01	3.1	<0.1	<0.05	2	<0.5	<0.2			
1595004	Rab Sample	0.008	43	2	0.06	194	0.012	<20	0.36	0.020	0.26	1.5	0.01	3.4	<0.1	<0.05	2	<0.5	<0.2			
1595005	Rab Sample	0.009	83	3	0.08	231	0.010	<20	0.41	0.019	0.26	0.3	0.02	4.2	0.1	<0.05	2	<0.5	<0.2			
1595006	Rab Sample	0.007	43	3	0.08	228	0.003	<20	0.40	0.014	0.25	1.9	0.02	3.7	<0.1	<0.05	2	<0.5	<0.2			
1595007	Rab Sample	0.007	46	3	0.05	168	0.001	<20	0.33	0.012	0.22	0.7	0.02	2.7	<0.1	<0.05	1	<0.5	<0.2			
1595008	Rab Sample	0.009	59	6	0.07	168	<0.001	<20	0.37	0.002	0.25	2.2	0.04	1.7	<0.1	<0.05	<1	<0.5	<0.2			
1595009	Rab Sample	0.008	65	4	0.07	180	<0.001	<20	0.34	0.009	0.23	0.6	0.04	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595010	Rab Sample	0.008	69	3	0.08	180	<0.001	<20	0.36	0.008	0.24	2.1	0.04	1.4	<0.1	<0.05	<1	0.5	<0.2			
1595011	Rab Sample	0.003	32	3	0.04	149	<0.001	<20	0.29	0.014	0.24	0.6	0.02	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595012	Rab Sample	0.007	52	3	0.04	152	<0.001	<20	0.29	0.008	0.25	1.7	0.02	1.3	0.1	<0.05	<1	<0.5	<0.2			
1595013	Rab Sample	0.005	48	3	0.06	186	<0.001	<20	0.35	0.010	0.24	0.8	0.02	2.2	0.2	<0.05	<1	<0.5	<0.2			
1595014	Rab Sample	0.006	57	3	0.11	202	<0.001	<20	0.43	0.005	0.27	2.7	0.04	2.4	0.1	<0.05	1	<0.5	<0.2			
1595015	Rab Sample	0.005	43	3	0.06	170	<0.001	<20	0.34	0.010	0.26	0.7	0.05	2.2	0.2	<0.05	1	<0.5	<0.2			
1595016	Rab Sample	0.006	41	3	0.05	146	<0.001	<20	0.31	0.015	0.24	1.4	0.02	2.2	<0.1	<0.05	1	<0.5	<0.2			
1595017	Rab Sample	0.006	43	4	0.07	151	0.002	<20	0.35	0.017	0.24	2.5	0.01	2.3	0.1	<0.05	2	<0.5	<0.2			
1595018	Rab Sample	0.008	54	4	0.06	156	0.002	<20	0.32	0.021	0.24	1.2	0.02	2.4	<0.1	<0.05	2	<0.5	<0.2			
1595019	Rab Sample	0.007	50	5	0.04	149	0.001	<20	0.32	0.021	0.25	1.1	<0.01	1.9	<0.1	<0.05	1	<0.5	<0.2			
1595020	Rock Pulp	0.044	9	71	1.40	164	0.138	<20	2.74	0.348	0.30	10.3	0.07	2.9	0.1	0.11	7	<0.5	<0.2			
1595021	Rab Sample	0.006	33	4	0.04	136	<0.001	<20	0.30	0.015	0.26	2.9	0.03	1.2	<0.1	<0.05	<1	<0.5	<0.2			
1595022	Rab Sample	0.007	35	4	0.03	139	<0.001	<20	0.27	0.013	0.23	1.0	0.03	1.4	<0.1	<0.05	<1	<0.5	<0.2			
1595023	Rab Sample	0.006	24	4	0.03	132	0.001	<20	0.25	0.021	0.22	2.7	<0.01	1.5	<0.1	<0.05	1	<0.5	<0.2			
1595024	Rab Sample	0.008	43	5	0.03	174	<0.001	<20	0.30	0.020	0.24	1.3	0.01	1.4	<0.1	<0.05	1	<0.5	<0.2			
1595025	Rab Sample	0.011	74	5	0.02	144	0.002	<20	0.27	0.021	0.22	2.8	0.02	1.6	<0.1	<0.05	<1	<0.5	<0.2			
1595026	Rab Sample	0.006	34	6	0.01	150	0.001	<20	0.23	0.027	0.26	1.7	0.01	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595027	Rab Sample	0.006	48	5	0.02	179	<0.001	<20	0.21	0.024	0.28	3.6	<0.01	1.3	<0.1	0.06	<1	<0.5	<0.2			
1595028	Rab Sample	0.008	30	5	0.01	161	0.002	<20	0.21	0.026	0.22	2.0	0.02	2.0	<0.1	<0.05	<1	<0.5	<0.2			
1595029	Rab Sample	0.010	90	5	0.02	174	0.001	<20	0.28	0.021	0.25	3.4	0.01	1.7	<0.1	<0.05	<1	<0.5	<0.2			
1595030	Rab Sample	0.011	90	5	0.02	165	0.001	<20	0.27	0.020	0.25	1.6	0.02	1.5	<0.1	<0.05	<1	<0.5	<0.2			



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 3 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1595031	Rab Sample	3.76	0.263	1.3	2.7	28.4	63	0.4	1.2	2.6	219	0.55	138.6	212.7	10.8	5	1.5	0.7	<0.1	<1	0.02
1595032	Rab Sample	3.76	0.016	1.1	1.9	26.5	68	0.3	1.1	0.6	58	0.57	82.2	15.0	13.0	5	0.6	0.7	<0.1	<1	0.02
1595033	Rab Sample	3.23	0.007	0.9	1.8	13.7	27	0.3	0.9	0.6	33	0.51	41.0	3.1	12.3	5	0.3	0.5	<0.1	<1	0.02
1595034	Rab Sample	3.59	0.017	1.2	3.0	26.3	74	0.6	1.0	1.2	79	0.98	153.9	12.5	12.6	6	1.0	0.8	<0.1	<1	0.03
1595035	Rab Sample	3.34	0.022	0.9	2.0	31.2	48	0.3	0.7	0.6	43	0.67	178.7	15.3	12.9	6	0.7	0.8	0.2	<1	0.03
1595036	Rab Sample	3.35	0.017	0.9	2.4	20.7	65	0.2	1.0	0.8	66	0.76	57.8	13.3	13.1	6	0.4	0.3	0.1	<1	0.04
1595037	Rab Sample	3.33	0.029	1.1	2.3	19.2	57	0.1	1.1	0.8	74	0.81	146.9	22.3	13.5	6	0.8	0.6	0.1	<1	0.05
1595038	Rab Sample	3.78	0.017	1.1	2.7	19.3	71	0.3	1.0	0.6	82	0.82	139.3	14.9	13.5	7	0.9	0.7	<0.1	<1	0.04
1595039	Rab Sample	3.78	0.015	1.1	1.8	27.6	75	0.3	1.1	0.9	99	0.83	48.4	10.5	13.4	7	0.5	0.3	<0.1	<1	0.04
1595040	Rock Pulp	0.08	0.511	7.3	303.8	16.3	51	0.6	120.3	15.7	475	2.84	171.1	441.1	3.1	79	0.2	2.3	0.1	69	1.95
1595041	Rab Sample	3.47	0.016	1.3	2.4	20.2	46	0.2	1.0	0.5	52	0.67	130.9	13.4	12.6	5	0.6	0.6	<0.1	<1	0.03
1595042	Rab Sample	3.01	0.007	1.0	2.4	21.2	53	0.3	0.9	1.0	87	0.63	51.4	3.4	12.2	5	0.4	0.3	<0.1	<1	0.02
1595043	Rab Sample	3.22	0.007	1.2	3.3	25.7	59	0.2	1.0	0.9	104	0.73	59.9	4.9	13.4	5	0.6	0.3	<0.1	<1	0.03
1595044	Rab Sample	3.38	0.011	1.2	3.3	23.2	54	0.3	1.0	0.9	107	0.64	46.8	7.3	14.5	6	0.6	0.4	<0.1	<1	0.03
1595045	Rab Sample	3.39	0.010	1.1	1.9	20.4	29	0.1	0.7	0.4	75	0.48	58.3	4.2	12.3	5	0.4	0.4	<0.1	<1	0.02
1595046	Rab Sample	3.39	0.015	1.3	3.6	24.4	46	0.3	1.2	0.8	133	0.56	68.5	11.3	13.4	6	0.9	0.6	0.2	<1	0.03
1595047	Rab Sample	3.14	0.011	1.3	3.2	23.2	32	0.3	1.0	0.5	74	0.69	75.3	6.7	13.6	5	0.4	0.5	0.1	<1	0.02
1595048	Rab Sample	3.31	0.012	1.4	3.0	32.5	47	0.3	1.0	0.8	79	0.84	136.2	8.2	13.7	6	0.8	0.8	<0.1	<1	0.02
1595049	Rab Sample	2.97	0.011	1.2	2.7	25.2	34	0.2	0.8	0.2	38	0.73	88.8	6.6	12.6	5	0.5	0.6	<0.1	<1	0.02
1595050	Rab Sample	3.10	0.011	1.1	2.7	26.6	32	0.2	0.8	0.3	34	0.67	87.2	5.3	12.6	5	0.4	0.6	<0.1	<1	0.02
1595051	Rab Sample	3.76	0.008	1.1	2.9	27.2	81	0.3	1.0	0.7	157	0.76	49.5	4.3	12.1	7	0.6	0.4	<0.1	<1	0.04
1595052	Rab Sample	3.31	0.019	2.0	3.7	40.7	112	0.7	2.8	1.4	740	0.96	66.6	13.2	11.6	11	0.9	0.7	<0.1	1	0.07
1595053	Rab Sample	3.16	0.008	1.1	3.7	19.9	63	0.4	1.2	0.7	190	0.73	37.0	5.9	15.0	8	0.6	0.4	0.3	<1	0.04
1595054	Rab Sample	3.15	0.005	0.9	1.9	14.4	29	0.1	0.9	0.5	81	0.42	20.0	2.8	14.5	6	0.2	0.1	0.3	<1	0.03
1595055	Rab Sample	3.13	0.013	1.2	2.5	16.9	37	0.5	0.9	1.7	269	0.82	127.0	9.5	11.5	5	0.9	0.6	0.2	1	0.02
1595056	Rab Sample	2.42	0.013	1.1	3.8	11.9	38	0.4	1.2	1.3	165	1.10	226.1	10.8	16.8	7	1.9	0.6	0.3	1	0.03
1595057	Rab Sample	2.62	0.015	2.3	4.2	26.8	45	0.7	0.9	1.5	207	1.01	213.9	9.6	16.5	7	2.3	0.5	0.4	<1	0.04
1595058	Rab Sample	2.78	0.011	1.7	3.1	12.5	26	0.4	1.1	0.5	65	0.80	178.5	7.4	13.6	7	0.8	0.3	0.4	<1	0.04
1595059	Rab Sample	2.54	<0.005	1.9	2.8	14.5	17	0.3	1.0	0.8	84	0.64	34.4	1.9	14.1	46	0.6	0.2	0.4	<1	0.37
1595060	Rock Pulp	0.08	7.268	8.4	184.3	19.0	73	1.0	12.6	10.3	579	4.85	13.4	8795.8	2.4	82	0.2	5.0	0.6	115	1.00



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 3 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

	Method	Analyte	Unit	MDL	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200			
					P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
					%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
					0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
1595031	Rab Sample	0.007	52	5	0.02	156	<0.001	<20	0.24	0.009	0.25	2.8	0.03	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595032	Rab Sample	0.006	34	5	0.04	148	0.001	<20	0.26	0.021	0.23	2.3	0.02	1.9	<0.1	<0.05	<1	<0.5	<0.2			
1595033	Rab Sample	0.004	20	5	0.02	162	0.007	<20	0.28	0.029	0.26	4.4	<0.01	2.1	<0.1	<0.05	1	<0.5	<0.2			
1595034	Rab Sample	0.007	51	5	0.04	215	0.001	<20	0.35	0.024	0.25	1.8	0.01	2.1	<0.1	<0.05	1	<0.5	<0.2			
1595035	Rab Sample	0.005	43	4	0.04	173	<0.001	<20	0.34	0.020	0.27	2.6	0.02	2.0	0.3	<0.05	1	<0.5	<0.2			
1595036	Rab Sample	0.007	43	5	0.08	176	0.003	<20	0.38	0.021	0.29	1.4	<0.01	2.5	0.1	<0.05	2	<0.5	<0.2			
1595037	Rab Sample	0.008	37	6	0.08	157	0.004	<20	0.38	0.021	0.29	3.5	<0.01	2.2	0.1	<0.05	2	<0.5	<0.2			
1595038	Rab Sample	0.006	36	6	0.07	164	0.002	<20	0.37	0.018	0.28	1.4	0.01	2.4	<0.1	<0.05	2	<0.5	<0.2			
1595039	Rab Sample	0.006	45	6	0.06	197	0.002	<20	0.39	0.020	0.29	3.7	0.01	2.7	0.1	<0.05	2	<0.5	<0.2			
1595040	Rock Pulp	0.035	8	113	1.44	122	0.092	<20	2.73	0.332	0.22	1.0	0.05	2.9	<0.1	0.10	6	<0.5	<0.2			
1595041	Rab Sample	0.006	39	6	0.03	166	0.001	<20	0.30	0.019	0.26	1.6	0.02	1.7	<0.1	<0.05	1	<0.5	<0.2			
1595042	Rab Sample	0.007	54	5	0.03	182	0.002	<20	0.29	0.025	0.27	3.4	0.01	2.0	<0.1	<0.05	1	<0.5	<0.2			
1595043	Rab Sample	0.007	43	6	0.03	185	0.002	<20	0.28	0.026	0.26	2.1	0.02	2.0	<0.1	<0.05	<1	<0.5	<0.2			
1595044	Rab Sample	0.006	47	6	0.03	186	0.002	<20	0.25	0.027	0.25	2.9	<0.01	1.4	<0.1	<0.05	<1	<0.5	<0.2			
1595045	Rab Sample	0.005	35	4	0.02	161	0.001	<20	0.23	0.022	0.28	1.5	0.02	0.9	<0.1	<0.05	<1	<0.5	<0.2			
1595046	Rab Sample	0.006	50	6	0.03	169	0.001	<20	0.25	0.025	0.24	2.4	0.02	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595047	Rab Sample	0.006	51	7	0.02	161	0.001	<20	0.24	0.026	0.24	2.0	0.02	1.4	<0.1	<0.05	<1	<0.5	<0.2			
1595048	Rab Sample	0.008	47	6	0.03	179	<0.001	<20	0.30	0.023	0.26	2.9	0.01	1.8	<0.1	<0.05	<1	<0.5	<0.2			
1595049	Rab Sample	0.007	39	5	0.02	143	<0.001	<20	0.25	0.019	0.24	1.2	0.03	1.4	<0.1	<0.05	<1	<0.5	<0.2			
1595050	Rab Sample	0.007	38	5	0.02	135	<0.001	<20	0.25	0.018	0.24	1.6	0.02	1.3	<0.1	<0.05	<1	<0.5	<0.2			
1595051	Rab Sample	0.006	50	5	0.05	214	0.001	<20	0.31	0.019	0.25	1.9	0.02	2.4	<0.1	<0.05	1	<0.5	<0.2			
1595052	Rab Sample	0.007	57	9	0.10	381	0.001	<20	0.39	0.015	0.21	1.2	0.04	3.9	0.2	<0.05	2	<0.5	<0.2			
1595053	Rab Sample	0.006	49	5	0.04	226	0.001	<20	0.31	0.019	0.25	1.2	0.02	2.9	0.1	<0.05	1	<0.5	<0.2			
1595054	Rab Sample	0.006	46	4	0.04	168	0.001	<20	0.27	0.016	0.27	0.7	0.01	1.6	<0.1	<0.05	1	<0.5	<0.2			
1595055	Rab Sample	0.009	40	5	0.02	177	<0.001	<20	0.21	0.015	0.15	1.5	0.02	1.5	<0.1	<0.05	<1	<0.5	<0.2			
1595056	Rab Sample	0.009	61	5	0.04	159	<0.001	<20	0.28	0.005	0.27	0.5	0.03	1.7	0.1	<0.05	1	<0.5	<0.2			
1595057	Rab Sample	0.008	58	4	0.04	164	<0.001	<20	0.32	0.002	0.28	0.8	0.03	1.7	0.2	<0.05	1	<0.5	<0.2			
1595058	Rab Sample	0.004	39	5	0.04	182	<0.001	<20	0.30	0.004	0.24	0.7	0.04	1.5	<0.1	<0.05	<1	<0.5	<0.2			
1595059	Rab Sample	0.005	46	6	0.11	342	<0.001	<20	0.39	0.007	0.29	1.8	<0.01	3.3	0.1	0.12	1	<0.5	<0.2			
1595060	Rock Pulp	0.060	8	16	0.84	124	0.134	<20	1.81	0.189	0.23	4.8	0.21	3.6	<0.1	<0.05	6	<0.5	<0.2			



**BUREAU** MINERAL LABORATORIES  
**VERITAS** Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 4 of 4

**Part:** 1 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

	Method	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
	Unit	kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
1595061	Rab Sample	2.62	<0.005	1.7	2.0	8.6	9	0.2	0.8	0.5	59	0.63	12.6	7.0	12.9	42	0.2	0.1	0.2	<1	0.40
1595062	Rab Sample	2.10	<0.005	2.5	3.1	11.9	7	0.2	0.9	0.6	68	0.62	7.2	4.3	11.3	100	0.3	0.5	0.2	<1	0.96
1595063	Rab Sample	1.96	<0.005	1.7	3.1	11.3	10	0.2	0.8	0.4	83	0.52	12.9	3.9	7.4	93	0.3	0.7	0.2	<1	0.75



**BUREAU VERITAS** MINERAL LABORATORIES  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 4 of 4

**Part:** 2 of 2

# CERTIFICATE OF ANALYSIS

WHI18000211.1

Method	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te	
Unit	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	
MDL	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2	
1595061	Rab Sample	0.005	37	6	0.07	417	<0.001	<20	0.36	0.005	0.29	1.4	<0.01	2.7	<0.1	0.10	1	<0.5	<0.2
1595062	Rab Sample	0.005	35	7	0.04	695	0.003	<20	0.42	0.015	0.29	2.3	<0.01	2.5	0.1	0.07	1	<0.5	<0.2
1595063	Rab Sample	0.005	24	6	0.02	555	0.005	<20	0.35	0.017	0.19	3.0	<0.01	1.8	<0.1	<0.05	1	<0.5	<0.2



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 1 of 2

**Part:** 1 of 2

## QUALITY CONTROL REPORT

WHI18000211.1

	Method Analyte Unit MDL	WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1
Pulp Duplicates																					
1595027	Rab Sample	4.00	0.042	1.2	1.3	19.9	10	0.2	0.9	0.5	22	0.50	127.8	33.4	12.8	9	<0.1	0.6	<0.1	<1	0.02
REP 1595027	QC		0.049	1.2	1.2	19.6	10	0.2	0.9	0.5	22	0.51	127.4	33.4	12.9	9	<0.1	0.5	<0.1	<1	0.02
1595029	Rab Sample	3.68	0.060	1.1	3.5	36.7	69	0.3	1.1	2.8	140	0.59	105.6	49.7	13.2	6	0.8	0.7	0.1	1	0.02
REP 1595029	QC		0.077																		
1595055	Rab Sample	3.13	0.013	1.2	2.5	16.9	37	0.5	0.9	1.7	269	0.82	127.0	9.5	11.5	5	0.9	0.6	0.2	1	0.02
REP 1595055	QC			1.2	2.4	16.4	33	0.5	1.2	1.7	259	0.80	123.4	9.2	10.9	5	0.9	0.7	0.2	1	0.02
Core Reject Duplicates																					
1595016	Rab Sample	3.15	0.012	0.7	2.5	13.5	46	0.2	0.9	0.6	42	0.66	100.3	11.2	12.8	6	0.9	0.5	<0.1	<1	0.03
DUP 1595016	QC		0.012	0.8	2.8	13.7	44	0.2	1.1	0.6	44	0.64	101.5	7.1	13.0	6	0.9	0.7	0.2	1	0.03
1595050	Rab Sample	3.10	0.011	1.1	2.7	26.6	32	0.2	0.8	0.3	34	0.67	87.2	5.3	12.6	5	0.4	0.6	<0.1	<1	0.02
DUP 1595050	QC		0.011	1.2	2.8	27.4	32	0.2	1.0	0.3	34	0.68	90.8	4.8	13.1	5	0.5	0.6	<0.1	<1	0.02
Reference Materials																					
STD DS11	Standard			12.9	159.1	136.6	311	1.7	79.0	12.6	958	3.13	40.6	65.9	7.3	66	2.1	7.3	11.8	49	1.06
STD DS11	Standard			15.2	162.8	135.2	339	1.6	80.0	13.7	1022	3.08	42.0	75.7	7.5	67	2.4	9.2	10.8	51	1.02
STD DS11	Standard			14.4	146.9	134.5	336	1.7	79.4	13.9	1026	3.04	44.5	61.1	7.6	69	2.6	6.3	11.0	50	1.07
STD OREAS45EA	Standard			1.8	726.5	16.1	35	0.3	407.0	52.3	408	25.07	13.1	58.2	11.3	4	<0.1	0.3	0.3	337	0.03
STD OREAS45EA	Standard			1.8	727.9	15.6	32	0.2	410.4	55.8	422	22.28	11.7	59.7	10.8	4	<0.1	0.5	0.3	313	0.03
STD OREAS45EA	Standard			1.5	720.5	13.5	31	0.2	376.0	53.7	402	22.54	11.1	56.9	10.2	4	<0.1	0.2	0.3	305	0.03
STD OXC145	Standard		0.214																		
STD OXC145	Standard		0.209																		
STD OXH139	Standard		1.322																		
STD OXH139	Standard		1.320																		
STD OXN134	Standard		7.701																		
STD OXN134	Standard		7.615																		
STD OXN134 Expected			7.667																		
STD OXC145 Expected			0.212																		
STD OXH139 Expected			1.312																		
STD OREAS45EA Expected				1.6	709	14.3	31.4	0.26	381	52	400	22.65	11.4	53	10.7	4.05	0.03	0.32	0.26	303	0.036





**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

Client:

**White Gold Corp.**

Box 70

Dawson Yukon Y0B 1G0 Canada

Project:

BZA

Report Date:

July 26, 2018

Page:

1 of 2

Part:

2 of 2

## QUALITY CONTROL REPORT

WHI18000211.1

		AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
Method	Analyte	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Hg	Sc	Tl	S	Ga	Se	Te
Unit		%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm
MDL		0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5	0.2
Pulp Duplicates																			
1595027	Rab Sample	0.006	48	5	0.02	179	<0.001	<20	0.21	0.024	0.28	3.6	<0.01	1.3	<0.1	0.06	<1	<0.5	<0.2
REP 1595027	QC	0.006	50	5	0.02	182	<0.001	<20	0.21	0.025	0.29	3.9	<0.01	1.2	<0.1	0.06	<1	<0.5	<0.2
1595029	Rab Sample	0.010	90	5	0.02	174	0.001	<20	0.28	0.021	0.25	3.4	0.01	1.7	<0.1	<0.05	<1	<0.5	<0.2
REP 1595029	QC																		
1595055	Rab Sample	0.009	40	5	0.02	177	<0.001	<20	0.21	0.015	0.15	1.5	0.02	1.5	<0.1	<0.05	<1	<0.5	<0.2
REP 1595055	QC	0.008	39	5	0.02	184	<0.001	<20	0.20	0.014	0.15	1.6	0.03	1.6	<0.1	<0.05	<1	<0.5	<0.2
Core Reject Duplicates																			
1595016	Rab Sample	0.006	41	3	0.05	146	<0.001	<20	0.31	0.015	0.24	1.4	0.02	2.2	<0.1	<0.05	1	<0.5	<0.2
DUP 1595016	QC	0.006	42	3	0.05	145	<0.001	<20	0.31	0.015	0.23	1.6	0.02	2.3	<0.1	<0.05	1	<0.5	<0.2
1595050	Rab Sample	0.007	38	5	0.02	135	<0.001	<20	0.25	0.018	0.24	1.6	0.02	1.3	<0.1	<0.05	<1	<0.5	<0.2
DUP 1595050	QC	0.006	39	5	0.02	141	<0.001	<20	0.25	0.018	0.25	1.8	0.03	1.3	<0.1	<0.05	<1	<0.5	<0.2
Reference Materials																			
STD DS11	Standard	0.065	17	58	0.84	436	0.087	<20	1.14	0.072	0.40	2.7	0.23	3.3	4.9	0.27	5	2.0	4.5
STD DS11	Standard	0.074	19	61	0.83	369	0.091	<20	1.15	0.074	0.40	2.7	0.26	3.1	5.0	0.27	5	1.9	4.5
STD DS11	Standard	0.070	19	57	0.86	423	0.092	<20	1.19	0.075	0.40	2.5	0.25	3.3	5.1	0.28	5	2.5	4.6
STD OREAS45EA	Standard	0.031	8	933	0.09	172	0.098	<20	3.39	0.019	0.06	<0.1	0.01	88.7	<0.1	<0.05	13	2.0	<0.2
STD OREAS45EA	Standard	0.031	7	885	0.11	151	0.087	<20	3.40	0.025	0.06	<0.1	0.01	80.1	<0.1	<0.05	13	1.4	<0.2
STD OREAS45EA	Standard	0.031	7	841	0.10	135	0.097	<20	3.47	0.019	0.06	<0.1	0.02	82.1	<0.1	<0.05	13	1.8	<0.2
STD OXC145	Standard																		
STD OXC145	Standard																		
STD OXH139	Standard																		
STD OXH139	Standard																		
STD OXN134	Standard																		
STD OXN134	Standard																		
STD OXN134 Expected																			
STD OXC145 Expected																			
STD OXH139 Expected																			
STD OREAS45EA Expected		0.029	7.06	849	0.095	148	0.0984		3.32	0.02	0.053			78	0.072	0.036	12.4	0.78	0.1



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 2

**Part:** 1 of 2

## QUALITY CONTROL REPORT

WHI18000211.1

		WGHT	FA430	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200	AQ200
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	Au	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.5	0.1	1	0.1	0.1	0.1	1	0.01
STD DS11 Expected				13.9	149	138	345	1.71	77.7	14.2	1055	3.1	42.8	79	7.65	67.3	2.37	7.2	12.2	50	1.063
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	0.2	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01
Prep Wash																					
ROCK-WHI	Prep Blank		<0.005	0.9	4.2	1.1	37	<0.1	1.3	4.1	582	1.85	1.6	<0.5	2.1	33	<0.1	<0.1	<0.1	22	0.96
ROCK-WHI	Prep Blank		<0.005	1.0	4.1	1.0	37	<0.1	1.2	4.7	579	1.87	1.3	<0.5	2.0	27	<0.1	<0.1	<0.1	22	0.73



**BUREAU  
VERITAS**

**MINERAL LABORATORIES**  
Canada

[www.bureauveritas.com/um](http://www.bureauveritas.com/um)

Bureau Veritas Commodities Canada Ltd.

9050 Shaughnessy St Vancouver British Columbia V6P 6E5 Canada

PHONE (604) 253-3158

**Client:** **White Gold Corp.**  
Box 70  
Dawson Yukon Y0B 1G0 Canada

**Project:** BZA  
**Report Date:** July 26, 2018

**Page:** 2 of 2

**Part:** 2 of 2

## QUALITY CONTROL REPORT

WHI18000211.1

		AQ200 P % 0.001	AQ200 La ppm 1	AQ200 Cr ppm 1	AQ200 Mg % 0.01	AQ200 Ba ppm 1	AQ200 Ti % 0.001	AQ200 B ppm 20	AQ200 Al % 0.01	AQ200 Na % 0.001	AQ200 K % 0.01	AQ200 W ppm 0.1	AQ200 Hg ppm 0.01	AQ200 Sc ppm 0.1	AQ200 Tl ppm 0.1	AQ200 S % 0.05	AQ200 Ga ppm 1	AQ200 Se ppm 0.5	AQ200 Te ppm 0.2
STD DS11 Expected		0.0701	18.6	61.5	0.85	417	0.0976		1.129	0.0694	0.4	2.9	0.26	3.1	4.9	0.2835	4.7	2.2	4.56
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
BLK	Blank	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5	<0.2
Prep Wash																			
ROCK-WHI	Prep Blank	0.041	6	3	0.51	64	0.075	<20	1.05	0.078	0.10	<0.1	<0.01	2.8	<0.1	<0.05	4	<0.5	<0.2
ROCK-WHI	Prep Blank	0.039	7	3	0.52	64	0.082	<20	1.05	0.097	0.11	5.1	<0.01	2.9	<0.1	0.06	4	<0.5	<0.2